

	<u>from</u>	<u>to</u>	<u>width</u> <u>(feet)</u>	<u>assay</u> <u>(% U₃O₈)</u>
1) Uranium				
B-12	123.7	129.3	5.6	.004
(con't.)	129.3	129.9	0.6	.005
	129.9	130.8	0.9	.013
	130.8	131.2	0.4	.018
	131.2	132.4	1.3	.146
	132.4	133.4	1.0	.004
	133.4	137.5	3.9	.004
	137.5	138.8	1.3	.006
	138.8	141.1	2.3	.193
	141.1	142.4	1.3	.006
	142.4	144.7	2.3	.001
	144.7	148.0	3.3	.003
	148.0	149.3	1.3	.025
	149.3	150.0	0.7	.010
	150.0	154.0	4.0	.012
B-13	139.5	141.0	1.5	.026
	141.0	142.0	1.0	.057
	142.0	143.3	1.3	.116
	143.3	144.7	1.4	.002
	144.7	148.0	4.3	.001
	148.0	152.0	4.0	.001
	<u>from</u>	<u>to</u>	<u>width</u> <u>(feet)</u>	<u>assay</u> <u>(% Cu)</u>
2) Copper				
B-5	134.0	135.0	1.0	.08
	135.0	136.1	1.1	.31
	136.1	138.5	2.4	.84
	138.5	139.0	0.5	.16
	139.0	140.0	1.0	.04
B-12	69.0	70.0	1.0	.01
	70.0	71.0	1.0	.15
	71.0	71.9	0.9	.44
	71.9	73.6	1.7	.39
	73.6	75.0	1.4	.07
	75.0	77.6	2.6	.05
	77.6	78.8	1.2	.04
	78.8	79.9	1.1	.40
	79.9	81.2	1.3	.15
	81.2	82.8	1.6	.08
	82.8	84.0	1.2	.19

	from	to	width (feet)	assay (% Cu)
2) Copper				
B-12	84.0	85.8	1.8	.11
(con't.)	85.8	87.2	1.4	.20
	87.2	89.1	1.9	.23
	89.1	90.8	1.7	.30
	90.8	91.5	0.7	.54
	91.5	92.4	0.9	.05
	92.7	93.9	1.2	.01
	93.9	95.1	1.2	.01
	95.1	96.8	1.7	.02
	96.8	99.0	2.2	.03
	99.0	100.0	1.0	.01
	100.0	100.5	0.5	.03
	100.5	104.0	3.5	.03
	104.0	105.3	1.3	.41
	105.3	106.3	1.0	.75
	106.3	107.6	1.3	.01
	107.6	108.3	0.7	.01
	108.3	108.6	0.3	.02
	108.6	109.9	1.3	.01
	109.9	122.8	1.1	.01
	122.8	123.7	0.9	.01
	123.7	129.3	5.6	.02
	129.3	129.9	0.6	.01
	129.9	130.8	0.9	.01
	130.8	131.2	0.4	.01
	131.2	132.4	1.3	.01
	132.4	133.4	1.0	.07
	133.4	137.5	3.9	.09
	137.5	138.8	1.3	.02
	138.8	141.1	2.3	.13
	141.1	142.4	1.3	.01
	142.4	144.7	2.3	.23
	144.7	148.0	3.3	.79
	148.0	149.3	1.3	.31
	149.3	150.0	0.7	.44
	150.0	154.0	4.0	.21
B-13	88.0	93.0	4.0	.10
	93.0	98.0	5.0	.10
	98.0	103.0	5.0	.06
	103.0	108.0	5.0	.01
	108.0	113.0	5.0	.04
	113.0	118.0	5.0	.05
	118.0	123.0	5.0	.01
	123.0	128.0	5.0	.01
	128.0	133.0	5.0	.01
	133.0	137.0	4.0	.01
	137.0	139.5	2.5	.06