

Appendix A

DRILL CORE ASSAYS

	<u>from</u>	<u>to</u>	<u>width</u> <u>(feet)</u>	<u>assay</u> <u>(% U₃O₈)</u>
1) Uranium				
B-5	134.0	135.0	1.0	.011
	135.0	136.1	1.1	.023
	136.1	138.5	2.4	.142
	138.5	139.0	0.5	.087
	139.0	140.0	1.0	.018
B-12	69.0	70.0	1.0	.007
	70.0	71.0	1.0	.087
	71.0	71.9	0.9	.584
	71.9	73.6	1.7	.132
	73.6	75.0	1.4	.021
	75.0	77.6	2.6	.001
	77.6	78.8	1.2	.001
	78.8	79.9	1.1	.017
	79.9	81.2	1.3	.081
	81.2	82.8	1.6	.080
	82.8	84.0	1.2	.157
	84.0	85.8	1.8	.091
	85.8	87.2	1.4	.124
	87.2	89.1	1.9	.146
	89.1	90.8	1.7	.052
	90.8	91.5	0.7	.125
	91.5	92.4	0.9	.014
	92.4	92.7	0.3	.082
	92.7	93.9	1.2	.007
	93.9	95.1	1.2	.032
	95.1	96.8	1.7	.018
	96.8	99.0	2.2	.006
	99.0	100.0	1.0	.001
	100.0	100.5	0.5	.088
	100.5	104.0	3.5	.004
	104.0	105.3	1.3	.165
	105.3	106.3	1.0	.083
	106.3	107.6	1.3	.014
	107.6	108.3	0.7	.010
	108.3	108.6	0.3	.031
	108.6	109.9	1.3	.003
	121.7	122.8	1.1	.005
	122.8	123.7	0.9	.063

	<u>from</u>	<u>to</u>	<u>width (feet)</u>	<u>assay (% U₃O₈)</u>
1) Uranium				
B-12	123.7	129.3	5.6	.004
(con't.)	129.3	129.9	0.6	.005
	129.9	130.8	0.9	.013
	130.8	131.2	0.4	.018
	131.2	132.4	1.3	.146
	132.4	133.4	1.0	.004
	133.4	137.5	3.9	.004
	137.5	138.8	1.3	.006
	138.8	141.1	2.3	.193
	141.1	142.4	1.3	.006
	142.4	144.7	2.3	.001
	144.7	148.0	3.3	.003
	148.0	149.3	1.3	.025
	149.3	150.0	0.7	.010
	150.0	154.0	4.0	.012
B-13	139.5	141.0	1.5	.026
	141.0	142.0	1.0	.057
	142.0	143.3	1.3	.116
	143.3	144.7	1.4	.002
	144.7	148.0	4.3	.001
	148.0	152.0	4.0	.001
	<u>from</u>	<u>to</u>	<u>width (feet)</u>	<u>assay (% Cu)</u>
2) Copper				
B-5	134.0	135.0	1.0	.08
	135.0	136.1	1.1	.31
	136.1	138.5	2.4	.84
	138.5	139.0	0.5	.16
	139.0	140.0	1.0	.04
B-12	69.0	70.0	1.0	.01
	70.0	71.0	1.0	.15
	71.0	71.9	0.9	.44
	71.9	73.6	1.7	.39
	73.6	75.0	1.4	.07
	75.0	77.6	2.6	.05
	77.6	78.8	1.2	.04
	78.8	79.9	1.1	.40
	79.9	81.2	1.3	.15
	81.2	82.8	1.6	.08
	82.8	84.0	1.2	.19