

# SAMPLE LOG

HOLE: GK-10-01

From (m)	To (m)	Interval (m)	Recovery (m)	Recovery (%)	Sample	Batch	Au (g/t)	Ag (g/t)	Cu (ppm)	Mo (ppm)	As (ppm)	Bi (ppm)	Comments
0.00	11.27	11.27			N/S								Casing/Overburden
11.27	17.00	5.73	2.49	43	J997603	1	0.008	0.1	26	0.5	1	1	strongly weathered/poor recovery
17.00	22.02	5.02	2.07	41	J997604	1	0.011	0.1	46	0.5	2	1	strongly weathered/poor recovery
22.02	26.51	4.49	1.98	44	J997605	1	0.0025	0.1	64	0.5	2	1	strongly weathered/poor recovery
26.51	29.56	3.05	2.13	70	J997606	1	0.0025	0.2	94	0.5	1	1	strongly weathered/poor recovery
					J997607	1	0.0025	0.1	4	0.5	1	2	Blank
29.56	36.00	6.44	2.43	38	J997608	1	0.0025	0.1	64	0.5	2	1	poor recovery
36.00	38.71	2.71	2.67	99	J997609	1	0.0025	0.2	45	0.5	1	1	
38.71	41.78	3.07	1.73	56	J997610	1	0.0025	0.1	59	0.5	1	1	
41.78	44.80	3.02	2.03	67	J997611	1	0.012	0.1	61	0.5	1	1	
44.80	47.72	2.92	2.39	82	J997612	1	0.0025	0.1	22	0.5	1	2	
					J997613	1	0.222	2	1915	149	24	7	Standard: CDN-CGS-23
47.72	50.90	3.18	2.15	68	J997614	1	0.0025	0.1	51	0.5	3	1	partial cave material
50.90	53.95	3.05	2.94	96	J997615	1	0.0025	0.2	32	0.5	1	1	
53.95	57.00	3.05	2.04	68	J997616	1	0.023	0.1	34	2	4	3	
57.00	60.05	3.05	3.10	100	J997617	1	0.048	0.2	91	0.5	1	3	
60.05	63.67	3.62	3.54	98	J997618	1	0.0025	0.1	93	0.5	1	1	
63.67	65.98	2.31	1.38	60	J997619	1	0.0025	2.1	66	2	6	2	cave/fault?
65.98	69.19	3.21	2.57	80	J997620	1	0.009	0.1	164	0.5	1	2	
					J997621	1	0.233	150	2530	4	5500	15	Standard: CDN-ME-7
69.19	72.24	3.05	2.72	89	J997622	1	0.011	0.3	250	0.5	3	4	
72.24	75.29	3.05	2.80	92	J997623	1	0.0025	0.1	152	0.5	1	3	
75.29	77.35	2.06	1.89	92	J997624	1	0.0025	0.1	122	0.5	1	1	
77.35	79.94	2.59	2.42	93	J997625	1	0.077	0.1	75	1	3	1	dyke
					J997626	1	0.016	0.1	59	1	2	1	Quarter split duplicate of ***626
79.94	83.00	3.06	2.23	73	J997627	1	0.005	0.1	59	1	1	1	dyke
83.00	87.48	4.48	3.40	76	J997628	1	0.071	0.1	104	0.5	1	4	poor recovery
87.48	90.53	3.05	2.31	78	J997629	1	0.0025	0.1	81	0.5	1	1	END of HQ @ 90.53m
90.53	93.00	2.47	2.64	100	J997630	1	0.016	0.1	93	5	1	3	dyke
93.00	96.73	3.73	3.04	84	J997631	1	0.026	0.1	175	0.5	3	2	fault?
					J997632	1	0.0025	0.1	6	0.5	1	3	Blank
96.73	99.67	2.94	2.72	93	J997633	1	0.192	0.2	127	1	4	1	
99.67	102.92	3.25	2.71	83	J997634	1	0.182	0.2	423	2	2	4	
102.92	104.18	1.26	1.17	93	J997635	1	0.066	0.1	181	3	5	3	
104.18	106.61	2.43	1.52	63	J997636	1	0.7	0.1	153	7	29	1	
106.61	108.19	1.58	1.40	89	J997637	1	0.349	0.1	398	2	8	5	
108.19	111.32	3.13	2.43	78	J997638	1	0.102	0.1	621	6	4	3	shear
111.32	114.91	3.59	3.32	92	J997639	2	0.012	0.1	97	0.5	1	1	
114.91	117.96	3.05	2.39	78	J997640	2	0.011	0.1	98	0.5	1	1	
117.96	121.01	3.05	2.29	75	J997641	2	0.0025	0.1	77	0.5	1	1	
121.01	123.88	2.87	2.46	86	J997642	2	0.0025	0.1	86	0.5	1	1	fault
					J997643	2	0.259	1.9	2050	163	29	4	Standard: CDN-CGS-23
123.88	127.10	3.22	2.34	73	J997644	2	0.325	0.1	519	29	4	1	fault
127.10	131.00	3.90	2.66	68	J997645	2	0.313	0.1	492	8	9	1	
131.00	133.20	2.20	2.07	94	J997646	2	0.012	0.1	116	0.5	1	1	
133.20	136.25	3.05	2.74	90	J997647	2	0.006	0.1	65	0.5	3	1	
136.25	139.56	3.31	2.90	88	J997648	2	0.008	0.1	207	0.5	1	1	
					J997649	2	0.0025	0.1	133	0.5	1	1	Quarter split duplicate of ***649
139.56	142.34	2.78	2.60	94	J997650	2	0.0025	0.1	126	0.5	3	1	
142.34	145.39	3.05	2.77	91	J997651	2	0.0025	0.1	105	0.5	1	1	
145.39	148.44	3.05	2.60	90	J997652	2	0.0025	0.1	96	0.5	2	1	
148.44	149.71	1.27	1.32	100	J997653	2	0.026	0.1	258	31	3	1	
149.71	152.12	2.41	2.38	100	J997654	2	0.0025	0.1	76	0.5	2	1	
152.12	154.53	2.41	2.33	97	J997655	2	0.024	0.2	421	4	8	1	oxidized fault
					J997656	2	0.0025	0.1	2	0.5	3	1	blank
154.53	157.58	3.05	2.72	89	J997657	2	0.008	0.1	110	0.5	1	1	oxidized fault
157.58	161.00	3.42	3.29	96	J997658	2	0.0025	0.1	130	0.5	5	1	
161.00	164.42	3.42	3.20	94	J997659	2	0.06	0.1	541	5	2	1	
164.42	166.26	1.84	1.71	93	J997660	2	1.07	0.4	4650	74	6	1	increased mineralization
166.26	169.77	3.51	2.74	78	J997661	2	0.035	0.1	302	6	6	1	
169.77	172.82	3.05	2.96	99	J997662	2	0.283	0.1	738	69	6	1	

# SAMPLE LOG

From (m)	To (m)	Interval (m)	Recovery (m)	Recovery (%)	Sample	Batch	Au (g/t)	Ag (g/t)	Cu (ppm)	Mo (ppm)	As (ppm)	Bi (ppm)	Comments
172.82	173.56	0.74	0.80	100	J997663	2	13.1	11.6	60500	859	21	1	strong mineralization
					J997664	2	0.007	0.3	36	1	13	1	blank
173.56	175.87	2.31	2.18	96	J997665	2	0.05	0.1	686	11	7	1	
175.87	178.92	3.05	2.77	91	J997666	2	0.009	0.1	117	2	4	1	
178.92	181.68	2.76	2.58	93	J997667	2	0.011	0.1	166	1	3	1	
181.68	185.01	3.33	3.17	95	J997668	2	0.0025	0.1	52	0.5	3	1	
185.01	188.06	3.05	3.00	98	J997669	2	0.0025	0.1	92	0.5	5	1	
188.06	190.00	1.94	1.76	91	J997670	2	0.005	0.1	129	0.5	3	1	
					J997671	2	0.214	154	2540	3	6490	11	Standard: CDN-ME-7
190.00	192.73	2.73	2.03	74	J997672	2	0.0025	0.4	83	0.5	17	1	
192.73	194.16	1.43	1.26	88	J997673	2	0.0025	0.1	137	0.5	1	1	
194.16	197.21	3.05	2.43	80	J997674	2	0.0025	0.1	110	0.5	3	1	
197.21	200.25	3.04	2.95	97	J997675	3	0.006	0.1	125	0.5	6	1	
200.25	203.30	3.05	2.84	93	J997676	3	0.006	0.1	141	1	8	1	
203.30	206.35	3.05	2.97	97	J997677	3	0.0025	0.1	123	0.5	5	1	
206.35	209.40	3.05	2.79	91	J997678	3	0.0025	0.1	93	0.5	4	1	
209.40	212.32	2.92	2.68	92	J997679	3	0.0025	0.1	100	0.5	3	1	
212.32	215.49	3.17	2.76	87	J997680	3	0.019	0.1	180	4	13	1	
					J997681	3	0.008	0.1	2	1	3	1	Blank
215.49	217.29	1.80	1.73	96	J997682	3	0.086	0.1	564	6	7	1	
217.29	220.85	3.56	3.00	84	J997683	3	0.0025	0.1	139	0.5	5	1	
220.85	224.16	3.31	3.18	96	J997684	3	0.0025	0.1	151	0.5	3	1	
224.16	227.33	3.17	3.11	98	J997685	3	0.005	0.1	150	0.5	3	1	
227.33	230.50	3.17	2.97	94	J997686	3	0.0025	0.1	84	0.5	1	1	
230.50	233.59	3.09	2.98	96	J997687	3	0.005	0.1	108	0.5	5	1	
					J997688	3	0.0025	0.1	78	0.5	4	1	Quarter split duplicate of ***687
233.59	236.49	2.90	2.72	94	J997689	3	0.0025	0.1	58	0.5	6	1	
236.49	239.88	3.39	3.24	96	J997690	3	0.0025	0.1	95	0.5	1	1	
239.88	241.30	1.42	1.41	99	J997691	3	0.006	0.1	62	0.5	4	1	dyke?
241.30	243.87	2.57	2.47	96	J997692	3	0.0025	0.1	197	1	5	1	
					J997693	3	0.87	4.6	13050	188	21	1	Standard: CDN-CGS-21
243.87	246.53	2.66	2.48	93	J997694	3	0.011	0.1	115	0.5	2	1	
246.53	249.02	2.49	2.48	100	J997695	3	0.005	0.1	74	0.5	3	1	
249.02	250.73	1.71	1.75	100	J997696	3	0.009	0.2	204	1	4	1	
250.73	251.59	0.86	0.83	98	J997697	3	0.013	0.4	232	2	235	1	dyke/fault?
					J997698	3	0.0025	0.2	5	1	3	1	Blank
251.59	252.50	0.91	0.89	98	J997699	3	0.0025	0.1	93	1	4	1	
252.50	255.12	2.62	2.58	98	J997700	3	0.0025	0.2	124	1	9	1	
255.12	258.17	3.05	2.91	97	J997701	3	0.0025	0.1	91	0.5	5	1	
258.17	260.00	1.83	1.95	100	J997702	3	0.024	0.2	268	3	7	1	
260.00	262.33	2.33	2.40	100	J997703	3	0.01	0.2	138	1	3	1	
262.33	265.66	3.33	3.05	95	J997704	3	0.102	0.4	308	30	6	1	
265.66	268.03	2.37	2.46	100	J997705	3	0.167	0.2	22	18	4	1	strongly fractured, healed
					J997706	3	0.435	2.1	4580	240	109	1	Standard: CDN-CM-7
268.03	269.98	1.95	1.84	94	J997707	3	0.005	0.2	71	1	1	1	
269.98	273.41	3.43	3.05	89	J997708	3	0.006	0.3	92	1	1	1	
273.41	276.45	3.04	2.98	98	J997709	3	0.005	0.2	102	1	5	1	
276.45	279.50	3.05	2.95	97	J997710	3	0.0025	0.2	93	0.5	1	1	
279.50	281.19	1.69	1.61	96	J997711	4	0.005	0.2	53	0.5	5	1	
281.19	284.10	2.91	3.00	100	J997712	4	0.0025	0.3	107	0.5	5	1	
284.10	287.19	3.09	3.00	97	J997713	4	0.005	0.2	93	0.5	3	1	
					J997714	4	0.0025	0.3	67	0.5	4	1	Quarter split duplicate of ***713
287.19	290.19	3.00	2.94	98	J997715	4	0.011	0.2	125	6	2	1	
290.19	293.20	3.01	2.89	97	J997716	4	0.012	0.4	204	0.5	5	1	
293.20	295.72	2.52	2.58	100	J997717	4	0.0025	0.3	67	0.5	4	2	
295.72	298.72	3.00	2.90	98	J997718	4	0.019	0.1	99	0.5	2	1	
298.72	301.94	3.22	3.20	99	J997719	4	0.007	0.1	120	0.5	1	1	
					J997720	4	0.235	2.2	1890	148	28	2	Standard: CDN-CGS-23
301.94	303.89	1.95	1.89	97	J997721	4	0.0025	0.2	56	0.5	1	1	
303.89	306.93	3.04	2.96	97	J997722	4	0.0025	0.1	31	0.5	1	1	
306.93	309.98	3.05	3.05	100	J997723	4	0.0025	0.1	57	0.5	5	2	
309.98	312.00	2.02	2.01	100	J997724	4	0.005	0.2	142	0.5	14	1	

# SAMPLE LOG

From (m)	To (m)	Interval (m)	Recovery (m)	Recovery (%)	Sample	Batch	Au (g/t)	Ag (g/t)	Cu (ppm)	Mo (ppm)	As (ppm)	Bi (ppm)	Comments
312.00	313.03	1.03	1.15	100	J997725	4	0.005	0.2	73	0.5	11	1	
					J997726	4	0.0025	0.4	3	0.5	1	1	Blank
313.03	316.08	3.05	3.10	100	J997727	4	0.006	0.4	184	0.5	11	1	
316.08	319.57	3.49	3.13	92	J997728	4	0.017	0.4	345	2	151	1	
319.57	322.17	2.60	2.73	100	J997729	4	0.005	0.2	129	0.5	5	1	
322.17	325.22	3.05	2.76	93	J997730	4	0.007	0.5	166	0.5	11	1	
325.22	328.27	3.05	2.99	98	J997731	4	0.0025	0.2	85	0.5	4	1	
328.27	331.32	3.05	3.02	99	J997732	4	0.007	0.4	189	0.5	4	1	
331.32	334.37	3.05	2.99	98	J997733	4	0.008	0.1	175	0.5	12	1	
334.37	337.97	3.60	3.60	100	J997734	4	0.0025	0.1	97	0.5	6	1	
337.97	340.46	2.49	2.11	85	J997735	4	0.0025	0.1	130	0.5	2	1	alteration envelope
340.46	343.20	2.74	2.56	93	J997736	4	0.007	0.1	277	9.5	5	1	shear with lower envelope
					J997737	4	0.0025	0.1	5	1	2	1	Blank
343.20	345.34	2.14	2.15	100	J997738	4	0.005	0.1	44	0.5	1	1	
345.34	347.51	2.17	2.17	100	J997739	4	0.01	0.1	143	0.5	2	1	
347.51	350.09	2.58	2.39	93	J997740	4	0.009	0.1	146	0.5	3	1	
350.09	352.65	2.56	2.47	96	J997741	4	0.008	0.1	181	0.5	3	1	
352.65	355.40	2.75	2.47	93	J997742	4	0.006	0.1	121	0.5	4	1	
355.40	357.10	1.70	1.85	100	J997743	4	0.009	0.1	117	0.5	4	1	volcaniclastics(?)
					J997744	4	0.234	2	1900	151	27	1	Standard: CDN-CGS-23
357.10	358.75	1.65	1.85	100	J997745	4	0.005	0.1	109	0.5	3	1	
358.75	361.80	3.05	3.05	100	J997746	4	0.0025	0.1	119	0.5	5	1	
361.80	364.85	3.05	2.93	97	J997747	5	0.006	0.1	167	0.5	17	1	
364.85	367.39	2.54	2.60	100	J997748	5	0.006	0.1	59	0.5	4	1	
367.39	370.41	3.02	3.12	100	J997749	5	0.0025	0.1	85	0.5	8	1	
					J997750	5	0.0025	0.1	73	0.5	6	1	Quarter split duplicate of ***749
370.41	373.38	2.97	2.91	99	J997751	5	0.0025	0.1	65	0.5	1	1	
373.38	376.46	3.08	2.99	97	J997752	5	0.0025	0.1	64	0.5	2	1	
376.46	379.43	2.97	2.99	100	J997753	5	0.005	0.1	116	0.5	3	1	
379.43	382.36	2.93	2.94	100	J997754	5	0.006	0.1	109	2	5	1	
382.36	385.33	2.97	2.99	100	J997755	5	0.0025	0.1	58	1	4	1	
					J997756	5	0.0025	0.1	<1	0.5	1	1	Blank
385.33	388.33	3.00	3.05	100	J997757	5	0.0025	0.1	61	0.5	3	1	
388.33	391.33	3.00	2.95	98	J997758	5	0.0025	0.1	54	0.5	3	1	
391.33	394.33	3.00	2.92	97	J997759	5	0.0025	0.1	50	0.5	2	1	
394.33	397.32	2.99	2.29	80	J997760	5	0.0025	0.1	171	1	3	1	
397.32	399.59	2.27	2.38	100	J997761	5	0.006	0.1	88	1	1	1	
399.59	401.42	1.83	1.82	99	J997762	5	0.007	0.1	95	0.5	2	1	
					J997763	5	0.986	4.8	13200	192	21	9	Standard: CDN-CGS-21
401.42	404.47	3.05	3.05	100	J997764	5	0.006	0.1	118	0.5	1	1	
404.47	407.56	3.09	3.09	100	J997765	5	0.005	0.1	43	2	5	1	
407.56	409.69	2.13	2.03	95	J997766	5	0.012	0.1	76	0.5	4	1	minor rubble zone
409.69	412.74	3.05	3.06	100	J997767	5	0.007	0.1	80	0.5	2	1	
412.74	415.91	3.17	3.03	96	J997768	5	0.022	0.1	247	0.5	5	1	healed shear(?) zone
					J997769	5	0.0025	0.1	1	0.5	1	1	Blank
415.91	418.77	2.86	2.87	100	J997770	5	0.006	0.1	156	0.5	2	1	
418.77	419.71	0.94	0.91	97	J997771	5	0.016	0.1	146	0.5	5	1	
419.71	422.76	3.05	2.95	97	J997772	5	0.0025	0.1	117	0.5	4	1	
422.76	425.81	3.05	2.99	98	J997773	5	0.035	0.2	351	0.5	1	1	
					J997774	5	0.423	2.1	4600	239	105	1	Standard: CDN-CM-7
425.81	427.41	1.60	1.59	99	J997775	5	0.048	0.4	252	0.5	4	1	
427.41	429.36	1.95	1.94	99	J997776	5	0.0025	0.1	104	0.5	4	1	
429.36	431.90	2.54	2.50	98	J997777	5	0.0025	0.1	70	0.5	1	1	
431.90	433.55	1.65	1.64	100	J997778	5	0.005	0.1	147	0.5	2	1	
433.55	434.95	1.40	1.63	100	J997779	5	0.018	5.9	217	0.5	8	1	some possible gouge
434.95	438.00	3.05	3.01	100	J997780	5	0.006	0.1	145	0.5	3	1	
438.00	441.05	3.05	3.04	100	J997781	5	0.0025	0.1	147	0.5	2	1	
441.05	444.09	3.04	3.05	100	J997782	5	0.005	0.3	150	0.5	1	1	
444.09	447.14	3.05	2.97	97	J997783	6	0.006	0.1	168	0.5	1	1	
447.14	450.19	3.05	3.02	99	J997784	6	0.006	0.1	168	0.5	1	1	
450.19	453.24	3.05	2.98	98	J997785	6	0.011	0.2	166	0.5	14	1	
453.24	456.29	3.05	2.97	97	J997786	6	0.007	0.1	137	0.5	1	1	

# SAMPLE LOG

From (m)	To (m)	Interval (m)	Recovery (m)	Recovery (%)	Sample	Batch	Au (g/t)	Ag (g/t)	Cu (ppm)	Mo (ppm)	As (ppm)	Bi (ppm)	Comments
456.29	459.42	3.13	3.12	100	J997787	6	0.022	0.3	347	1	5	1	
					J997788	6	0.013	0.4	292	1	2	1	Quarter split duplicate of ***787
459.42	461.66	2.24	2.28	100	J997789	6	0.0025	0.1	176	0.5	4	1	porphyritic dyke
461.66	464.12	2.46	2.50	100	J997790	6	0.008	0.1	158	0.5	1	1	
464.12	466.28	2.16	2.19	100	J997791	6	0.014	0.2	309	1	3	1	
466.28	469.17	2.89	2.83	98	J997792	6	0.096	0.4	324	1	2	1	
469.17	472.10	2.93	2.88	98	J997793	6	0.009	0.2	153	0.5	1	1	
					J997794	6	0.187	2	1885	152	22	1	Standard: CDN-CGS-23
472.10	473.30	1.20	1.15	98	J997795	6	0.018	0.4	434	1	9	1	shearing
473.30	474.57	1.27	1.41	100	J997796	6	0.008	0.3	190	0.5	1	1	
474.57	477.67	3.10	3.04	100	J997797	6	0.013	0.3	304	0.5	3	1	
477.67	479.96	2.29	2.26	99	J997798	6	0.011	0.2	194	0.5	4	1	intense irregular fracturing
					J997799	6	0.005	0.1	4	0.5	4	1	Blank
479.96	482.91	2.95	2.90	100	J980300	6	0.006	0.1	126	0.5	1	1	
482.91	484.51	1.60	1.65	100	J980301	6	0.007	0.2	200	0.5	1	1	
484.51	487.42	2.91	2.91	100	J980302	6	0.005	0.2	161	0.5	2	1	
487.42	489.00	1.58	1.61	100	J980303	6	0.007	0.1	144	0.5	1	1	
489.00	490.42	1.42	1.46	100	J980304	6	0.005	0.3	163	0.5	1	1	
490.42	493.25	2.83	2.76	100	J980305	6	0.005	0.3	184	0.5	1	1	
493.25	496.39	3.14	3.13	100	J980306	6	0.0025	0.1	164	0.5	1	1	
496.39	498.07	1.68	1.73	100	J980307	6	0.0025	0.3	163	0.5	1	1	
					J980308	6	0.415	2.3	4620	249	107	1	Standard: CDN-CM-7
498.07	501.23	3.16	3.05	100	J980309	6	0.0025	0.2	178	0.5	5	1	
501.23	503.10	1.87	1.95	100	J980310	6	0.005	0.1	137	0.5	5	1	
503.10	504.93	1.83	2.00	100	J980311	6	0.0025	0.2	143	0.5	2	1	
504.93	506.82	1.89	1.91	100	J980312	6	0.0025	0.1	133	0.5	1	1	
506.82	509.08	2.26	2.18	98	J980313	6	0.066	0.1	169	0.5	2	1	minor shear/fault zone
					J980314	6	0.0025	0.1	4	0.5	6	1	Blank
509.08	511.15	2.07	2.10	100	J980315	6	0.006	0.1	132	0.5	3	1	
511.15	514.20	3.05	3.11	100	J980316	6	0.005	0.3	183	0.5	1	1	
514.20	517.25	3.05	3.02	100	J980817	6	0.0025	0.1	182	0.5	1	1	
517.25	520.29	3.04	2.85	97	J980318	6	0.006	0.1	167	0.5	1	1	
520.29	522.42	2.13	2.23	100	J980319	7	0.005	0.3	212	0.5	3	1	
522.42	524.32	1.90	1.71	90	J980320	7	0.0025	0.2	205	0.5	2	1	
524.32	526.39	2.07	2.02	98	J980321	7	0.0025	0.5	157	0.5	12	1	
					J980322	7	0.196	2	1900	146	27	2	Standard: CDN-CGS-23
526.39	529.44	3.05	3.01	99	J980323	7	0.017	0.3	374	0.5	4	1	
529.44	532.49	3.05	2.61	86	J980324	7	0.0025	0.1	115	0.5	25	1	
532.49	535.53	3.04	1.44	47	J980325	7	0.022	0.1	157	0.5	5	1	EOH @ 535.53m