



# BONDAR-CLEGG & COMPANY LTD.

764 BELFAST ROAD, OTTAWA, ONTARIO, K1G 0Z5 PHONE: 237-3110 TELEX: 053-3548

## Certificate of Analysis

RECEIVED  
JUL 22 1974

TO Cordilleran Engineering Limited  
1418-355 Burrard Street  
Vancouver, B.C.

REPORT NO. A 44-26  
DATE July 19, 1974  
Project # BAF-GOZ

I hereby certify that the following are the results of analyses made by us upon the herein described Drill Core samples

74-1

MARKED	Zn T	Zn S							
	%	%							
14001	3.32	3.32							
14002	0.85	0.85							
14003	1.11	1.08							
14004	3.20	3.20							
14005	3.40	3.40							
14006	3.40	3.40							
14007	1.32	1.32							
14008	0.74	0.62							
14009	6.80	4.20							
14010	8.80	8.40							
14011	22.52	2.00							
14012	25.68	1.60							
14013	9.40	8.40							
14014	31.50	27.60							
14015	32.40	4.80							
14016	32.40	2.00							
14017	30.00	0.82							
14018	3.40	0.46							
14019	4.00	1.10							
14020	0.40	0.32							

ORIGINAL  
FILE COPY  
DO NOT REMOVE

APPENDIX "E"  
(Part A)

NOTE:  
Rejects retained two weeks  
Pulps retained three months  
unless otherwise arranged.

BONDAR-CLEGG & COMPANY LTD.

  
R. A. Pittuck Chief Chemist



# BONDAR-CLEGG & COMPANY LTD.

764 BELFAST ROAD, OTTAWA, ONTARIO, K1G 0Z5 PHONE: 237-3110 TELEX: 053-3548

RECEIVED  
AUG 1 1974

## Certificate of Analysis

TO J. W. Sillery  
CORDILLERAN ENG. LTD.  
1418-355 Burrard St. Van. B.C.

REPORT NO. A-44-41  
DATE 29-7-74  
PROJECT BAF-GOZ

I hereby certify that the following are the results of analyses made by us upon the herein described drill core samples

74-2,3


MARKED	% Zn	% Zn.							
	Total	soluble							
14021	8.56	5.84							
14022	29.20	3.20							
14023	14.96	4.32							
14024	4.80	3.52							
14025	5.60	2.96							
14026	5.04	0.61							
14027	2.16	0.44							
14028	18.64	0.26							
14029	2.40	0.27							
14030	5.36	0.15							
14031	10.40	1.92							
14032	6.40	1.06							
14033	1.40	0.46							

NOTE:  
Rejects retained two weeks  
Pulps retained three months  
unless otherwise arranged.

BONDAR-CLEGG & COMPANY LTD.

R. A. Pittuck, Chief Chemist

APPENDIX "E"  
(Part A)



# BONDAR-CLEGG & COMPANY LTD.

764 BELFAST ROAD, OTTAWA, ONTARIO, K1G 0Z5 PHONE: 237-3110 TELEX: 053-3548

RECEIVED  
AUG 1 1974

## Certificate of Analysis

TO Page 2

REPORT NO. A-44-41  
DATE 29-7-74

PROJECT BAF-GOZ

I hereby certify that the following are the results of analyses made by us upon the herein described drill core samples

74-2-3

MARKED	%Zn	%Zn							
	TOT.	SOL.							
14034	1.51	0.91							
14035	5.76	4.32							
14036	18.00	2.08							
14037	1.41	0.80							
14038	15.20	2.92							
14039	27.20	1.80							
14040	25.20	3.76							
14041	43.60	0.60							
14042	21.60	0.24							
14043	13.20	1.76							
14044	1.72	1.28							
14045	19.36	16.40							
14046	18.24	7.80							
14047	30.00	1.09							

NOTE:  
Rejects retained two weeks  
Pulps retained three months  
unless otherwise arranged.

BONDAR-CLEGG & COMPANY LTD.

APPENDIX "E"  
(Part A)  
111



# BONDAR-CLEGG & COMPANY LTD.

764 BELFAST ROAD, OTTAWA, ONTARIO, K1G 0Z5 PHONE: 237-3110 TELEX: 053-3548

## Certificate of Analysis



TO Page 3.

REPORT NO. A-44-41

DATE 29-7-74

PROJECT BAF-60Z


I hereby certify that the following are the results of analyses made by us upon the herein described drill core samples

MARKED	% Zn	% Cu							
	TOT	SOL							
140 48	40.40	0.27							
140 49	34.00	0.54							
140 50	2.72	1.84							
140 51	0.28	0.14							

APPENDIX "E"  
(part A)

NOTE:  
Rejects retained two weeks  
Pulps retained three months  
unless otherwise arranged.

BONDAR-CLEGG & COMPANY LTD.



# BONDAR-CLEGG & COMPANY LTD.

764 BELFAST ROAD, OTTAWA, ONTARIO, K1G 0Z5 PHONE: 237-3110 TELEX: 053-8548

RECEIVED  
AUG 6 1974

## Certificate of Analysis

TO J. W. Stollery  
Cord. Eng Ltd.  
1418 - 355 Burrard St.  
Vancouver, B. C.

REPORT NO. A-44-57  
DATE 31-7-74

I hereby certify that the following are the results of analyses made by us upon the herein described Drill Core samples

74-2 & 4

MARKED	Zn	Zn							
	% Tot	% Sol							
14069	0.15	0.12							
14070	0.09	0.07							
14071	0.10	0.08							
14072	0.76	0.72							
14073	4.96	4.72							
14074	4.92	4.16							
14075	0.36	0.35							
14076	24.40	22.40							
14077	2.72	2.68							
14078	1.20	1.12							
14079	6.88	6.32							


APPENDIX "E"  
(Part A)

NOTE:

Rejects retained two weeks  
Pulps retained three months  
unless otherwise arranged.

BONDAR-CLEGG & COMPANY LTD.

*R. A. Pittuck*  
R. A. Pittuck, Chief Chemist



# BONDAR-CLEGG & COMPANY LTD.

784 BELFAST ROAD, OTTAWA, ONTARIO, K1G 0Z5 PHONE: 237-3110 TELEX: 053-3548

## Certificate of Analysis



TO J.W. Stollery  
Cordilleran Eng. Ltd.  
1418-355 Burrard St. Van BC.

REPORT NO. A 44-44  
DATE 29-7-74  
PROJECT - BAF-60Z

I hereby certify that the following are the results of analyses made by us upon the herein described drill core samples


74-4, 5

MARKED	% Zn	% Zn							
	TOTAL	SOLUBLE							
14052	2.40	1.39							
14053	4.05	1.10							
14054	2.24	1.80							
14055	32.00	7.60							
14056	45.28	1.10							
14057	44.32	0.74							
14058	37.36	0.39							
14059	14.00	2.00							
14060	39.04	0.61							
14061	22.00	0.13							
14062	35.44	0.20							
14063	31.52	0.15							
14064	2.20	0.70							

ORIGINAL  
FILE COPY  
DO NOT REMOVE  
APPENDIX "E"  
(Part A)

NOTE:  
Rejects retained two weeks  
Pulps retained three months  
unless otherwise arranged.

BONDAR-CLEGG & COMPANY LTD.



# Certificate of Analysis

TO Page 2

REPORT NO. A-44-44

DATE 29-7-74

PROJECT BAF-GOZ

I hereby certify that the following are the results of analyses made by us upon the herein described drill core samples


74-5

MARKED	% Zn	% Zn							
	TOT	S&L							
<u>14065</u>	<u>7.68</u>	<u>1.66</u>							
<u>14066</u>	<u>30.32</u>	<u>0.92</u>							
<u>14067</u>	<u>3.60</u>	<u>1.94</u>							
<u>14068</u>	<u>16.00</u>	<u>8.90</u>							

APPENDIX "E"  
(Part A)

NOTE:  
Rejects retained two weeks  
Pulps retained three months  
unless otherwise arranged.

BONDAR-CLEGG & COMPANY LTD.



# Certificate of Analysis

TO J.W. Stollery.  
Cordilleran Engineering Ltd.

REPORT NO. A-44-62

DATE 7-8-74


I hereby certify that the following are the results of analyses made by us upon the herein described drill core samples

MARKED	% Zn	% Zn	% Zn in (s)	ASSAY	FOOTAGE				
	TOTAL	SOL.		INTERVAL					
DDH #5	14080	1.68	0.90	0.78	20-50	30'			
	14081	0.75	0.49	0.26	50-69	19'			
	14082	1.28	0.80	0.48	69-91	22'			
	14083	3.32	2.90	0.42	91-115	24'			
	14084	8.44	7.06	1.38	115-136	21'			
	14085	4.80	3.96	0.84	136-149	13'			
	14086	3.40	2.08	1.32	182-203	21'			
	14087	0.98	0.92	0.06	203-223	20'			
DDH #6	14088	3.56	3.23	0.33	17-40	26'			
	14089	9.20	7.52	1.68	40-64	24'			
	14090	3.12	2.90	0.22	64-77	13'			
	14091	9.20	7.56	1.64	77-96	19'			
	14092	7.80	3.30	4.50	96-118	22'			
	14093	8.40	3.60	4.80	118-128	10'			

NOTE:  
Rejects retained two weeks  
Pulps retained three months  
unless otherwise arranged.


BONDAR-CLEGG & COMPANY LTD.

APPENDIX "E"  
(Part A)  
viii



# BONDAR-CLEGG & COMPANY LTD.

764 BELFAST ROAD, OTTAWA, ONTARIO, K1G 0Z5 PHONE: 237-3110 TELEX: 053-3548



## Certificate of Analysis

TO Mr. J. W. Stallery  
1418-355 Burrard St.  
Van. Bc.

REPORT NO. A-44-87  
DATE 14-8-74  
BAF-60Z

I hereby certify that the following are the results of analyses made by us upon the herein described core samples

74-6

MARKED	%	%							
	Zn T	Zn S							
<u>14092</u>	<u>7.90</u>	<u>3.20</u>							
<u>14093</u>	<u>8.56</u>	<u>3.45</u>							


*These are re-assays from report A44-62*

APPENDIX "E"  
(Part A)

NOTE:  
Rejects retained two weeks  
Pulps retained three months  
unless otherwise arranged.

BONDAR-CLEGG & COMPANY LTD.






# BONDAR-CLEGG & COMPANY LTD.

764 BELFAST ROAD, OTTAWA, ONTARIO, K1G 0Z5 PHONE: 237-3110 TELEX: 053-3548

## Certificate of Analysis



TO Mr. J. W. Stollery  
1418 - 355 (Cord. Eng.)  
Burrard St.  
Van.

REPORT NO. A-44-75  
DATE 14-8-74  
PROJECT: BAF-GOZ

I hereby certify that the following are the results of analyses made by us upon the herein described Core samples

74-9


MARKED	%Zn	%Zn							
	TOT	SOL							
14102	0.64	0.37							
14103	0.82	0.70							
14104	0.80	0.38							
14105	3.28	0.23							
14106	0.69	0.06							
14107	2.92	0.13							
14108	0.51	0.10							
14109	2.00	0.10							
14110	0.11	0.04							

ORIGINAL  
FILE COPY  
DO NOT REMOVE  
APPENDIX "E"  
(Part I A)

NOTE:  
Rejects retained two weeks  
Pulps retained three months  
unless otherwise arranged.


BONDAR-CLEGG & COMPANY LTD.

*[Signature]*  
R. A. Pittuck, Chief Chemist



# BONDAR-CLEGG & COMPANY LTD.

764 BELFAST ROAD, OTTAWA, ONTARIO, K1G 0Z5 PHONE: 237-3110 TELEX: 053-3548



## Certificate of Analysis

TO Mr. J. W. Stolkery  
1418-355 Burrard St.  
Vancouver Bc.

REPORT NO. A44-78

DATE 14-8-74

PROJECT - BAF-GOZ

I hereby certify that the following are the results of analyses made by us upon the herein described Core samples

74-10

MARKED	% Zn	% Zn							
	TOT	SOL							
14111	0.63	<del>0.44</del> 0.40							
14112	1.84	1.20							
14113	0.21	0.17							
14114	0.39	0.34							
14115	0.49	0.45							
14116	0.28	0.26							
14117	0.94	0.21							
14118	0.09	0.08							

ORIGINAL  
FILE COPY  
DO NOT REMOVE

APPENDIX "E"  
(Part A)  
x11

NOTE:  
Rejects retained two weeks  
Pulps retained three months  
unless otherwise arranged.

BONDAR-CLEGG & COMPANY LTD.

R. A. Pittuck Chief Chemist



# BONDAR-CLEGG & COMPANY LTD.

764 BELFAST ROAD, OTTAWA, ONTARIO, K1G 0Z5 PHONE: 237-3110 TELEX: 053-3548

## Certificate of Analysis

TO Cordilleran Engineering Limited  
1418 - 355 Burrard St.  
Vancouver, B.C.



REPORT NO. A 44-88

DATE August 27, 1974

I hereby certify that the following are the results of analyses made by us upon the herein described drill core samples -DOH 74-11

MARKED	Zn Tot.	Zn Sol.							
	%	%							
14119	0.05	0.04							
14120	0.06	0.04							
14121	0.06	0.04							
14122	0.06	0.05							
14123	0.06	0.05							
14124	0.07	0.06							
14125	0.11	0.08							
14126	0.10	0.07							
14127	0.08	0.06							
14128	5.72	5.36							
14129	2.00	0.90							
14130	3.84	3.56							
14131	0.24	0.23							
14132	2.72	2.32							
14133	0.87	0.80							
14134	0.37	0.37							
14135	0.15	0.14							
14136	0.05	0.03							
14137	0.09	0.05							
14138	0.07	0.06							


FILE COPY  
DO NOT REMOVE  
ORIGINAL

NOTE:  
Rejects retained two weeks  
Pulps retained three months  
unless otherwise arranged.

BONDAR-CLEGG & COMPANY LTD.

*[Signature]*  
Chief Chemist

APPENDIX "I"  
PART 4  
XIII



# BONDAR-CLEGG & COMPANY LTD.

764 BELFAST ROAD, OTTAWA, ONTARIO, K1G 0Z5 PHONE: 237-3110 TELEX: 053-3548

## Certificate of Analysis

Page #2

TO Same as page #1  
\_\_\_\_\_  
\_\_\_\_\_

RECEIVED  
AUG 3 01974

REPORT NO. ... A. 44-88 .....  
DATE ..... August 27, 1974 .....

I hereby certify that the following are the results of analyses made by us upon the herein described Drill Core ..... samples

MARKED	Zn Tot.	Zn Sol.							
	%	%							
14139	0.21	0.18							
14140	0.18	0.17							
14141	1.36	1.00							
14142	0.38	0.27							
14143	0.74	0.23							
14144	2.20	2.04							
14145	6.56	4.76							
14146	1.46	1.24							
14147	5.40	0.80							
14148	2.48	1.12							
14149	0.64	0.59							
14150	1.64	1.15							
14151	12.96	2.40							
14152	3.80	3.28							
14153	10.08	1.60							
14154	11.48	1.20							
14155	2.20	2.00							
14156	1.24	0.58							
14157	0.68	0.56							
14158	0.31	0.28							

NOTE:  
Rejects retained two weeks  
Pulps retained three months  
unless otherwise arranged.

BONDAR-CLEGG & COMPANY LTD.

R. A. Pittuck Chief Chemist .....

APPENDIX "E"  
(Part A)  
xiv



# Certificate of Analysis

TO Cordilleran Engineering Ltd.  
\_\_\_\_\_  
\_\_\_\_\_

RECEIVED  
AUG 30 1974

REPORT NO. .... A 44-88 .....

DATE ..... August 27, 1974 ...

I hereby certify that the following are the results of analyses made by us upon the herein described Drill Core ..... samples

MARKED	Zn Tot.	Zn Sol.							
	%	%							
14159	2.12	0.43							
14160	2.00	0.35							
14161	0.37	0.29							
14162	0.27	0.20							
14163	1.54	1.54							
14164	0.72	0.65							
14165	0.83	0.83							
14166	2.80	2.68							
14167	5.52	4.64							
14168	4.10	1.32							
14169	8.24	0.62							
14170	18.80	1.15							
14171	28.00	0.19							
14172	19.60	0.14							
14173	14.64	0.15							
14174	28.15	1.08							
14175	0.67	0.20							
14176	0.67	0.09							
14177	0.15	0.05							

NOTE:  
Rejects retained two weeks  
Pulps retained three months  
unless otherwise arranged.

BONDAR-CLEGG & COMPANY LTD.

.....  
D. A. Pittuck Chief Chemist .....

APPENDIX "E"  
(Part A)  
XV

To: \_\_\_\_\_

PAGE No. One

BONDAR-CLEGG & COMPANY LTD.

REPORT No. A 44 06

DATE: September 11, 1974

Cordilleran Engineering Limited  
1418 - 355 Burrard St.  
Vancouver, B.C.

CERTIFICATE OF ASSAY



I hereby certify that the following are the results of assays made by us upon the herein described Core Gov samples.

MARKED	GOLD		SILVER	Zn Tot.	Zn Sol.						TOTAL VALUE PER TON (2000 LBS.)
	Ounces per Ton	Value per Ton	Ounces per Ton	Percent	Percent	Percent	Percent	Percent	Percent		
14178				0.19	0.17						
14179				0.13	0.12						
14180				0.71	0.11						
14181				0.39	0.07						
14182				3.56	0.62						
14183	74-1			0.53	0.19						
14184				0.13	0.11						
14185				0.80	0.08						
14186				0.19	0.07						
14187				0.41	0.32						
14188				1.68	0.19						
14189				4.72	2.40						
14190				1.36	0.35						
14191				0.62	0.22						
14192				0.77	0.67						
14193	74-4			1.92	0.94						
14194				0.27	0.22						
14195				0.31	0.14						
14196				2.92	0.19						
14197				0.20	0.08						
14198				0.37	0.29						
14199				1.36	0.10						
14200				1.04	1.04						
14201				0.65	0.61						
14202	74-5			0.32	0.32						
14203				0.22	0.22						
14204				0.26	0.10						
14205				0.74	0.73						

ORIGINAL

FILE COPY

DO NOT REMOVE

*R. A. Pittuck*  
R. A. Pittuck Chief Chemist

APPENDIX "E" Part XVI





To: Coralan Engineering Ltd.

REPORT No A24 689

PAGE No. 1

**BONDAR-CLEGG & COMPANY LTD.**

DATE: Sept. 18, 1974

1418 - 355 Burrard Street  
 Vancouver, B.C.  
 Attention: Mr. J. W. Stollery

**CERTIFICATE OF ASSAY**

Samples submitted: Sept. 9, 1974  
 Results completed: Sept. 18, 1974  
 Project No. BAF - GOZ

I hereby certify that the following are the results of assays made by us upon the herein described ore samples. SEP 20 1974

MARKED	GOLD		SILVER	Total Zn	Non-Sulfide Zn						TOTAL VALUE PER TON (2000 LBS.)		
	Ounces per Ton	Value per Ton	Ounces per Ton	Percent	Percent	Percent	Percent	Percent	Percent				
14227	74-8			0.28	0.13					cc. Mr. O. S. Hairsine			
14228				0.34	0.09								
14229				0.28	0.10								
14230				0.19	0.08								
14231				0.06	0.04								
14232				0.07	0.02								
14233				0.03	0.02								
14234				0.03	0.01								
14259				74-13			0.04	0.03					
14260							0.04	0.03					
14261	0.04	0.03											
14262	0.03	0.02											
14263	0.02	0.02											
14264	0.02	0.01											
14265	0.04	0.02											
14266	0.02	0.01											
14267	0.02	0.01											
14268	0.02	0.01											
14269	0.17	0.02											
14270	0.03	0.01											
14271				0.02	0.01								

**ORIGINAL**

FILE COPY  
 DO NOT REMOVE

APPENDIX "E"  
 (Part A)

  
 Registered Assayer, Province of British Columbia

To: Columbia Engineering Ltd.

REPORT No                      - 697

PAGE No.                      1

**BONDAR-CLEGG & COMPANY LTD.**

DATE:                      Sept. 25, 1974

1418 - 355 Burrard Street  
Vancouver, B. C.  
Attn: Mr. J. Stollery

**CERTIFICATE OF ASSAY**

Samples submitted: Sept. 11, 1974  
Results completed: Sept. 25, 1974

PROJECT: BAF-GOZ - 74-14


I hereby certify that the following are the results of assays made by us upon the herein described                      core                      samples.

MARKED	GOLD		SILVER	Total Zn	Non-sulphide		Pb	Percent	Percent	Percent	TOTAL VALUE PER TON (2000 LBS.)
	Ounces per Ton	Value per Ton	Ounces per Ton	Percent	Zn	Sb	Percent				
14272				0.07	0.06	-	-				
14273				0.36	0.35	-	-				
14274				0.24	0.23	-	-				
14275				1.95	1.75	-	-				
14276				0.90	0.80	-	-				
14277				2.75	2.70	-	-				
14278				4.50	4.45	-	-				
14279				5.60	5.30	-	-				
14280				5.40	4.40	-	-				
14281				3.35	0.38	0.17	0.55				
14282				10.95	0.15	1.05	2.50				
14283				8.85	0.75	0.53	1.55				
14284				16.05	2.60	0.17	0.50				
14285				25.20	1.45	0.80	1.85				
14286				38.60	2.45	0.22	0.70				
14287				12.80	0.50	0.37	1.00				
14288				10.05	0.36	0.15	0.35				
14289				15.00	0.50	0.18	0.45				
14290				1.30	0.70	-	-				
14291				3.80	3.65	-	-				
14292				0.75	0.45	-	-				
14293				0.15	0.11	-	-				
14294				1.55	0.95	-	-				
14295				0.30	0.11	-	-				
14296				0.08	0.05	-	-				
14297				0.75	0.07	-	-				

ORIGINAL  
FILE COPY  
DO NOT REMOVE

APPENDIX "E"  
(Part A)

Registered Assayer, Province of British Columbia



XX


**CERTIFICATE OF ASSAY**


*I hereby certify* that the following are the results of assays made by us upon the herein described core samples.

MARKED	GOLD		SILVER	Total Zn	Non-sulphide Zn						TOTAL VALUE PER TON (2000 LBS.)
	Ounces per Ton	Value per Ton	Ounces per Ton	Percent	Percent	Percent	Percent	Percent	Percent		
14298				0.48	0.21						
14299				0.23	0.09						
14300				0.41	0.40						
14301				0.59	0.27						
14302				1.95	0.26						
14303				0.66	0.07						
14304				3.80	0.06						
14305				1.60	0.04						
14306				0.41	0.04						
14307				2.95	0.07						
14308				0.49	0.10						
14309				0.33	0.06						
14310				0.90	0.10						
14311				0.17	0.06						
14312				0.20	0.03						
14313				14.10	0.16						
14314				0.39	0.04						
14315				1.00	0.04						
14316				0.90	0.04						
14317				0.11	0.02						
14318				13.05	0.07						
14319				0.24	0.03						
14320				0.10	0.02						
14321				1.00	0.03						
14322				0.39	0.02						
14323				0.03	0.01						

cc Mr. O. Hairsine

APPENDIX "E"  
(Part A)

  
Registered Assayer, Province of British Columbia



# BONDAR-CLEGG & COMPANY LTD.

1500 PEMBERTON AVE., NORTH VANCOUVER, B.C. PHONE: 985-0681 TELEX: 04-54554

RECEIVED  
SEP 27 1974

## Certificate of Analysis

TO Cordilleran Engineering Ltd.  
1418 - 355 Burrard Street  
Vancouver, B. C.

Report No: A24 - 726

Sept. 27/74

PROJECT: BAF-GOZ

I hereby certify that the following are the results of assays made by us upon the herein described core samples.

74-11  
74-12

MARKED	PERCENT	PERCENT	MARKED	PERCENT	PERCENT	MARKED	PERCENT	PERCENT
	Zn Total	Zn*		Zn Total	Zn*		PERCENT	PERCENT
14324	1.60	0.21	14342	0.07	0.04			
14325	0.08	0.05	14343	0.03	0.02			
14326	0.44	0.07	14344	0.09	0.02			
14327	0.24	0.06	14345	0.34	0.02			
14328	0.68	0.10	14346	0.03	0.02			
14329	0.16	0.07	14347	0.04	0.02			
14330	0.17	0.11	14348	0.03	0.02			
14331	0.88	0.10	14349	0.02	0.01			
14332	0.15	0.03	14350	0.18	0.02			
14333	1.40	0.07	14351	4.30	0.06			
14334	0.42	0.19	14352	0.08	0.01			
14335	2.15	0.73	14353	0.82	0.03			
14336	0.63	0.45	14354	0.60	0.02			
14337	0.15	0.05	14355	0.09	0.02			
14338	0.09	0.05	14356	0.04	0.02			
14339	0.09	0.05	14357	0.08	0.01			
14340	0.29	0.23	14358	0.53	0.03			
14341	0.11	0.10	14359	0.06	0.02			

\*nonsulphide  
cc Mr. O. Hairsine

ORIGINAL

### NOTE:

Rejects retained two weeks  
Pulps retained three months  
unless otherwise arranged.

BONDAR-CLEGG & COMPANY LTD  
REGISTERED ASSAYER, PROVINCE OF B.C.

*Handwritten signature*

APPENDIX "E"  
(Part A)  
XXII

To: Cord. Loran Engineering Ltd.


REPORT No     A     -733

PAGE No.     1    

BONDAR-CLEGG & COMPANY LTD.

DATE:     Sept. 27, 1974    

1418 - 355 Burrard Street  
Vancouver, B. C.



CERTIFICATE OF ASSAY

Samples submitted: Sept. 20, 1974  
Results completed: Sept. 27, 1974

Attn: Mr. J. Stollery

PROJECT: BAF-GOZ

74-15-16-

I hereby certify that the following are the results of assays made by us upon the herein described     core     samples.

MARKED	GOLD		SILVER	Total Zn	Zn*	Pb	Sb				TOTAL VALUE PER TON (2000 LBS.)
	Ounces per Ton	Value per Ton	Ounces per Ton	Percent	Percent	Percent	Percent	Percent	Percent		
14360				0.20	0.16	-	-				
14361				0.10	0.08	-	-				
14362				0.68	0.41	-	-				
14363				0.17	0.14	-	-				
14364				0.05	0.04	-	-				
14365				0.07	0.06	-	-				
14366				0.71	0.09	0.05	0.01				
14367				0.10	0.04	10.05	0.01				
14368				0.29	0.05	-	-				
14369				0.04	0.03	-	-				
14370				0.19	0.15	-	-				
14371				1.35	0.57	-	-				
14372				0.25	0.20	-	-				
14373				0.06	0.05	-	-				
14374				0.05	0.04	-	-				
14375				0.08	0.05	-	-				
14376				1.25	0.22	-	-				
14377				0.46	0.10	-	-				
14378				1.00	0.36	-	-				
14379				3.05	0.39	-	-				
14380				3.95	0.84	-	-				
14381				0.41	0.22	-	-				
14382				0.34	0.20	-	-				
14383				0.14	0.05	-	-				
14384				0.80	0.53	-	-				
14385				0.18	0.15	-	-				

ORIGINAL  
FILE COPY  
DO NOT REMOVE

APPENDIX "E" (Part A)

*[Signature]*  
Registered Assayer, Province of British Columbia

## CERTIFICATE OF ASSAY

I hereby certify that the following are the results of assays made by us upon the herein described core samples.

MARKED	GOLD		SILVER	Total Zn	Zn*						TOTAL VALUE PER TON (2000 LBS.)
	Ounces per Ton	Value per Ton	Ounces per Ton	Percent	Percent	Percent	Percent	Percent	Percent		
14386				3.10	0.75						
14387				0.59	0.49						
14388				4.25	0.74						
14389				2.05	0.73						
14390				0.66	0.28						
14391				0.42	0.20						
14392				0.55	0.33						
14393				0.53	0.15						
14394				0.19	0.04						
14395				0.19	0.06						
14396				2.95	0.06						
14397				0.21	0.10						
14398				0.47	0.29						
14399				1.20	0.38						
14400				0.30	0.24						
14401				0.08	0.04						
14402				0.29	0.10						
14403				0.39	0.07						
14404				0.45	0.25						
14405				0.66	0.53						
14406				0.65	0.60						
14407				0.07	0.06						
14408				0.05	0.01						
14409				0.11	0.01						
14410				2.15	0.05						
14411				0.55	0.03						

**CERTIFICATE OF ASSAY**

*I hereby certify* that the following are the results of assays made by us upon the herein described core samples.

MARKED	GOLD		SILVER	Total Zn	Zn*						TOTAL VALUE PER TON (2000 LBS.)
	Ounces per Ton	Value per Ton	Ounces per Ton	Percent	Percent	Percent	Percent	Percent	Percent		
14412				0.13	0.02						
14413				0.04	0.01						
14414				0.29	0.01						
14415				0.25	0.01						
14416				0.15	0.01						
14417				2.20	0.04						
14418				2.50	0.06						
14419				2.05	0.04						
14420				0.08	0.02						
14421				1.20	0.03						
14422				0.07	0.01						
14458				0.11	0.08						
14459				0.03	0.01						
14460				0.02	0.01						


cc Mr. O. Hairsine  
L denotes 'less than'

APPENDIX "E"  
(Part A)

xxxv

Registered Assayer, Province of British Columbia





## Certificate of Analysis

TO Gordilleran Engineering Ltd.

Report No: A24 - 769

October 8, 1974

PROJECT: BAF-GOZ

PAGE 2

I hereby certify that the following are the results of assays made by us upon the herein described \_\_\_\_\_ core \_\_\_\_\_ samples.


MARKED	PERCENT	PERCENT	MARKED	PERCENT	PERCENT	MARKED	PERCENT	PERCENT
	Zn	Zn*		Zn	Zn*		Zn	Zn*
14480	0.12	0.02	14499	0.07	0.05	14518	3.45	0.27
14481	0.37	0.07	14500	0.91	0.72	14519	0.85	0.07
14482	0.40	0.03	14501	0.07	0.06	14520	0.39	0.08
14483	0.11	0.02	14502	0.10	0.08	14521	2.35	0.81
14484	0.71	0.05	14503	4.00	1.00	14522	0.33	0.22
14485	0.04	0.02	14504	0.36	0.22	14523	0.58	0.30
14486	1.20	1.15	14505	0.20	0.13	14524	0.20	0.13
14487	0.24	0.22	14506	0.62	0.48	14525	1.80	0.31
14488	0.10	0.08	14507	0.05	0.04	14526	0.12	0.08
14489	0.07	0.06	14508	0.26	0.25	14527	0.04	0.04
14490	0.05	0.05	14509	0.24	0.20	14528	0.21	0.08
14491	0.07	0.06	14510	1.40	0.96	14529	2.40	0.15
14492	0.05	0.05	14511	0.89	0.59	14530	0.59	0.08
14493	0.07	0.06	14512	18.30	1.55	14531	0.12	0.02
14494	0.09	0.07	14513	18.40	1.50	14532	0.74	0.09
14495	0.19	0.15	14514	1.60	0.19	14533	1.60	0.16
14496	0.14	0.12	14515	0.10	0.04	14534	0.65	0.07
14497	0.06	0.05	14516	5.90	0.25	14535	0.04	0.02
14498	0.05	0.04	14517	0.69	0.13	14536	0.72	0.29

**NOTE:**

Rejects retained two weeks  
Pulps retained three months  
unless otherwise arranged.

BONDAR-CLEGG & COMPANY LTD.

REGISTERED ASSAYER, PROVINCE OF BRITISH COLUMBIA



# BONDAR-CLEGG & COMPANY LTD.

1500 PEMBERTON AVE., NORTH VANCOUVER, B.C. PHONE: 985-0681 TELEX: 04-54554

## Certificate of Analysis

TO Cordilleran Engineering Ltd.  
\_\_\_\_\_  
\_\_\_\_\_

Report No: A24 - 769

October 8, 1974

PROJECT: BAF-GOZ

PAGE 3

I hereby certify that the following are the results of assays made by us upon the herein described core samples.

MARKED	PERCENT	PERCENT	MARKED	PERCENT	PERCENT	MARKED	PERCENT	PERCENT
	Zn	Zn*						
14537	0.06	0.02						
14538	0.10	0.02						
cc Mr. O. Hairsine *nonsulphide Zn			<p>ORIGINAL FILE COPY DO NOT REMOVE</p>					

**NOTE:**

Rejects retained two weeks  
Pulps retained three months  
unless otherwise arranged.

BONDAR-CLEGG & COMPANY LTD.  
REGISTERED ASSAYER, PROVINCE OF BRITISH COLUMBIA

APPENDIX "E"  
(Part A)  
XXVII