

FROM

TO

DESCRIPTIONS

RAT CREEK 3 ASSAY INTERVAL NUMBERS

117½'	122½'	053918
122½'	127½'	053919
127½'	132½'	053920
132½'	137½'	053921
137½'	142'	053922
142'	146'	053923
146'	151'	053924
151'	156'	053925
156'	159½'	053926
159½'	165'	053927
165'	170'	053928
170'	175'	053929
175'	179½'	053930
179½'	183½'	053931
186'	192'	053932
192'	197'	053933
197'	200'	053934
200'	204'	053935
204'	209'	053936

Logged by: Oh Cady Hole Number: Reh 03 Sheet Number: 6



ALS Chemex

EXCELLENCE IN ANALYTICAL CHEMISTRY

ALS Canada Ltd.

212 Brooksbank Avenue

North Vancouver BC V7J 2C1

Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

CARLOS, ALLEN
275 ALSEK RD
WHITEHORSE YT Y1A 4T1

Page: 1
Finalized Date: 21-SEP-2006
Account: TFI

CERTIFICATE VA06077720

Project:

P.O. No.:

This report is for 35 Rock samples submitted to our lab in Vancouver, BC, Canada on 8-AUG-2006.

The following have access to data associated with this certificate:

ALLEN CARLOS

SAMPLE PREPARATION

ALS CODE	DESCRIPTION
WEI-21	Received Sample Weight
LOG-22	Sample login - Rcd w/o BarCode
CRU-QC	Crushing QC Test
CRU-31	Fine crushing - 70% <2mm
SPL-21	Split sample - riffle splitter
PUL-31	Pulverize split to 85% <75 um

ANALYTICAL PROCEDURES

ALS CODE	DESCRIPTION	
ME-MS41	50 element aqua regia ICP-MS	
Ag-AA46	Ore grade Ag - aqua regia/AA	AAS
Au-AA24	Au 50g FA AA finish	AAS

To: CARLOS, ALLEN
275 ALSEK RD
WHITEHORSE YT Y1A 4T1

This is the Final Report and supersedes any preliminary report with this certificate number. Results apply to samples as submitted. All pages of this report have been checked and approved for release.

Signature:

Keith Rogers, Executive Manager Vancouver Laboratory



ALS Chemex

EXCELLENCE IN ANALYTICAL CHEMISTRY

ALS Canada Ltd.

212 Brooksbank Avenue

North Vancouver BC V7J 2C1


Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

DR CARLOS, ALLEN
275 ALSEK RD
WHITEHORSE YT Y1A 4T1

Page: 2 - C
Total # Pages: 2 (A - D)
Finalized Date: 21-SEP-2006
Account: TFI

CERTIFICATE OF ANALYSIS VA06077720

Sample Description	Method Analyte Units LOR	ME-MS41	ME-MS41	ME-MS41	ME-MS41	ME-MS41	ME-MS41	ME-MS41	ME-MS41	ME-MS41	ME-MS41	ME-MS41	ME-MS41	ME-MS41	ME-MS41
		Ni	P	Pb	Rb	Re	S	Sb	Sc	Se	Sn	Sr	Ta	Te	Th
		ppm 0.2	ppm 10	ppm 0.2	ppm 0.1	ppm 0.001	% 0.01	ppm 0.05	ppm 0.1	ppm 0.2	ppm 0.2	ppm 0.2	ppm 0.01	ppm 0.01	ppm 0.2
B053918		45.0	1190	26.2	15.8	<0.001	0.10	0.50	7.0	0.2	0.6	129.5	0.01	<0.01	3.2
B053919		33.0	1440	11.3	20.0	<0.001	0.21	0.48	12.2	0.3	0.4	166.5	0.01	<0.01	2.7
B053920		18.9	1260	20.8	27.0	<0.001	0.04	0.51	3.9	0.3	0.5	97.0	<0.01	<0.01	3.5
B053921		18.4	780	23.8	17.5	<0.001	0.04	0.41	4.7	0.3	1.0	125.5	0.01	<0.01	4.5
B053922		18.7	660	19.2	16.8	<0.001	0.06	0.37	5.3	<0.2	0.8	101.5	<0.01	<0.01	5.5
B053923		37.3	1440	8.6	19.9	<0.001	0.09	0.90	11.5	<0.2	0.5	259.0	0.01	<0.01	1.3
B053924		22.9	1160	21.1	20.1	<0.001	0.03	0.47	5.1	0.3	0.9	96.2	<0.01	<0.01	5.4
B053925		14.9	700	27.7	11.5	<0.001	0.02	0.29	3.8	0.5	0.8	104.5	<0.01	<0.01	5.8
B053926		18.9	1100	19.3	19.9	<0.001	<0.01	0.37	6.1	0.3	0.7	168.0	0.01	0.01	3.8
B053927		17.4	1020	17.6	18.7	<0.001	<0.01	0.17	5.2	0.4	0.8	153.0	0.01	<0.01	4.0
B053928		25.3	2470	11.0	24.2	<0.001	<0.01	0.31	11.7	0.3	0.8	239.0	0.01	<0.01	2.4
B053929		25.6	2640	7.9	24.7	<0.001	<0.01	0.36	12.0	0.2	0.6	240.0	0.01	<0.01	2.6
B053930		25.1	2640	5.7	20.4	<0.001	<0.01	0.47	12.6	0.3	0.6	250.0	0.01	<0.01	2.6
B053931		23.1	2170	9.3	22.6	<0.001	<0.01	0.35	12.7	0.2	0.8	213.0	0.01	<0.01	3.5
B053932		2.0	70	52.1	29.4	<0.001	<0.01	0.31	1.4	0.5	2.8	57.7	0.02	<0.01	25.7
B053933		1.3	30	50.4	52.4	<0.001	<0.01	0.25	0.9	0.4	3.5	33.6	0.02	<0.01	30.3
B053934		0.7	10	54.4	63.7	<0.001	0.04	0.38	0.7	0.6	4.3	32.5	0.02	<0.01	34.5
B053935		0.7	20	54.3	81.1	<0.001	<0.01	0.58	0.9	0.3	5.5	27.8	0.02	<0.01	35.9
B053936		0.9	10	49.8	61.1	<0.001	0.06	0.72	0.8	0.5	4.2	35.1	0.02	<0.01	29.3
B053937		0.8	10	50.0	76.6	<0.001	0.26	1.93	0.8	0.8	4.4	22.3	0.02	<0.01	29.0
B053938		0.6	<10	43.3	74.7	0.001	0.23	0.97	1.2	2.3	4.2	18.9	0.03	0.01	23.8
B053939		1.3	30	49.7	75.4	<0.001	0.25	1.50	1.0	0.6	4.9	31.1	0.02	<0.01	29.6
B053940		9.9	470	35.4	36.2	<0.001	<0.01	0.54	3.7	0.5	1.9	116.5	0.02	<0.01	19.0
B053941		3.3	370	2.4	16.6	<0.001	<0.01	0.14	4.0	<0.2	0.3	42.4	<0.01	<0.01	13.5
B053942		12.2	560	37.7	57.9	<0.001	0.19	0.67	4.5	0.5	2.7	77.0	0.02	<0.01	21.6
B053943		7.6	300	45.1	24.4	<0.001	0.13	1.02	2.3	0.7	1.5	68.5	0.02	0.01	24.6
B053944		1.8	10	52.4	35.9	<0.001	0.47	0.74	0.7	0.9	2.2	39.2	0.02	0.01	31.0
B053945		1.4	10	54.1	50.3	<0.001	0.37	0.54	1.0	0.8	3.7	40.3	0.02	<0.01	34.2
B053946		14.1	650	20.3	23.3	<0.001	<0.01	0.17	4.0	0.2	1.6	97.3	0.01	<0.01	7.4
B053947		32.2	1310	15.6	21.5	<0.001	<0.01	0.38	8.7	0.2	0.9	119.0	0.01	<0.01	4.1
B053948		13.2	880	22.9	15.4	<0.001	0.05	0.25	3.6	0.8	0.9	129.0	0.01	0.01	9.9
B053949		21.6	1150	16.4	16.3	<0.001	0.06	0.24	5.6	0.8	0.9	182.5	0.01	<0.01	5.0
B053950		18.0	1210	15.7	15.5	<0.001	0.10	0.28	5.0	0.7	0.6	136.5	0.01	0.01	4.1
B053951		25.7	1170	15.6	18.3	<0.001	0.08	0.24	5.9	0.7	0.6	124.0	0.01	0.01	4.6
B053952		27.6	1720	13.0	16.5	<0.001	0.02	0.18	6.9	0.8	0.8	163.0	0.01	0.01	3.3

[illegible]