

PLACER DEVELOPMENT LIMITED

ATTN: D. M. Jenkins

LORING LABORATORIES LTD.

CERTIFICATE of COAL TESTING

FILE No. 17457

DATE: August 8, 1979

Page # 1

SAMPLE NO	IDENTIFICATION	SAMPLE TYPE	% RECOVERY			REC'D % H ₂ O	% H ₂ O	% VOL. MATTER	% ASH	% FIXED CARBON	% S	BTU /LB	F.S.I.	
			SINK	FLOAT										
58901	DDH 79-1	Raw Coal			Air Dried	-	14.92	43.97	30.13	21.16	.29	7253		
	50.9 - 52.4m				Dry Basis	-	-	46.06	31.69	22.25	.31	7501		
58902	DDH 79-1	Raw Coal			Air Dried	-	4.41	45.05	29.63	20.91	.44	7366		
	82.9 - 84.7m				Dry Basis	-	-	47.13	31.00	21.87	.46	7706		
58903	DDH 79-1	Raw Coal			Air Dried	-	3.69	20.15	70.85	5.31	.25	3069		
	98.1 - 98.7m				Dry Basis	-	-	20.92	73.56	5.52	.26	3118		
58904	DDH 79-1	Raw Coal			Air Dried	-	4.72	35.33	45.68	14.27	.26	5628		
	98.7 - 101m				Dry Basis	-	-	37.08	47.94	14.98	.27	4937		
58905	DDH 79-1	Raw Coal			Air Dried	-	5.76	49.61	22.31	22.32	.27	8722		
	101.7 - 103.6m				Dry Basis	-	-	52.64	23.67	23.69	.29	92.54		
58906	DDH 79-1	Raw Coal			Air Dried	-	6.87	44.37	22.96	25.80	.32	8140		
	113.4 - 114.9m				Dry Basis	-	-	47.64	24.65	27.71	.34	8740		
58907	DDH 79-1	Raw Coal			Air Dried	-	6.11	32.11	42.46	19.32	.24	5556		
	114.9 - 116.4m				Dry Basis	-	-	34.20	45.22	20.58	.26	5918		
5908	DDH 79-2	Raw Coal			Air Dried	-	6.65	40.56	33.53	19.26	.38	6559		
	29 - 29.8m				Dry Basis	-	-	43.45	35.92	20.63	.41	7026		