

PLACER DEVELOPMENT LIMITED

ATTN: D. M. Jenkins

LORING LABORATORIES LTD.

CERTIFICATE of COAL TESTING

FILE NO. 17457

DATE: August 8, 1979

Page # 1

SAMPLE NO	IDENTIFICATION	SAMPLE TYPE	% RECOVERY			REC'D % H ₂ O	% H ₂ O	% VOL. MATTER	% ASH	% FIXED CARBON	%	BTU /lb	F.S.I.
			SINK	FLOAT									
58901	DDH 79-1	Raw Coal			Air Dried	-	14.92	43.97	30.13	21.16	.29	7253	
	50.9 - 52.4m				Dry Basis	-	-	46.06	31.69	22.25	.31	7501	
58902	DDH 79-1	Raw Coal			Air Dried	-	4.41	45.05	29.63	20.91	.44	7366	
	82.9 - 84.7m				Dry Basis	-	-	47.13	31.00	21.87	.46	7706	
58903	DDH 79-1	Raw Coal			Air Dried	-	3.69	20.15	70.85	5.31	.25	8069	
	98.1 - 98.7m				Dry Basis	-	-	20.92	73.56	5.52	.26	8148	
58904	DDH 79-1	Raw Coal			Air Dried	-	4.72	35.33	45.68	14.27	.26	5628	
	98.7 - 101m				Dry Basis	-	-	37.08	47.94	14.98	.27	5937	
58905	DDH 79-1	Raw Coal			Air Dried	-	5.76	49.61	22.31	22.32	.27	8722	
	101.7 - 103.6m				Dry Basis	-	-	52.64	23.67	23.69	.29	92.54	
58906	DDH 79-1	Raw Coal			Air Dried	-	6.87	44.37	22.96	25.80	.32	8140	
	113.4 - 114.9m				Dry Basis	-	-	47.64	24.65	27.71	.34	8740	
58907	DDH 79-1	Raw Coal			Air Dried	-	6.11	32.11	42.46	19.32	.24	5556	
	114.9 - 116.4m				Dry Basis	-	-	34.20	45.22	20.58	.26	5918	
5908	DDH 79-2	Raw Coal			Air Dried	-	6.65	40.56	33.53	19.26	.38	6559	
	29 - 29.8m				Dry Basis	-	-	43.45	35.92	20.63	.41	7026	

PLACER DEVELOPMENT LIMITED

ATTN: D. M. Jenkins

LORING LABORATORIES LTD.

CERTIFICATE of COAL TESTING

FILE NO 17457

DATE August 2, 1979

Page # 2

SAMPLE NO	IDENTIFICATION	SAMPLE TYPE	% RECOVERY			REC'D % H ₂ O	INH % H ₂ O	% VOL. MATTER	% ASH	% FIXED CARBON	% S	B.T.U. /LB.	F.S.I.	
			SINK	FLOAT										
58909	DDH 79-2	Raw Coal			Air Dried	-	5.80	40.65	33.12	20.43	.14	7255		
	29.8 - 30.75m				Dry Basis	-	-	43.15	35.16	21.69	.15	7702		
58910	DDH 79-2	Raw Coal			Air Dried	-	3.61	24.47	64.06	7.86	.10	3325		
	31.7 - 32.6m				Dry Basis	-	-	25.39	66.46	8.15	.10	3450		
58911	DDH 79-2	Raw Coal			Air Dried	-	6.97	49.58	25.83	17.62	.23	7756		
	32.6 - 33.8 m				Dry Basis	-	-	53.29	27.77	18.94	.25	8337		
58912	DDH 79-2	Raw Coal			Air Dried	-	6.22	33.31	45.80	14.67	.13	4894		
	33.8 - 34.6m				Dry Basis	-	-	35.52	48.84	15.64	.14	5219		
58913	DDH 79-2	Raw Coal			Air Dried	-	4.35	24.92	59.76	10.97	.12	3510		
	34.0 - 35.1m				Dry Basis	-	-	26.05	62.48	11.47	.13	3670		
58914	DDH 79-2	Raw Coal			Air Dried	-	8.30	51.79	11.43	28.48	.40	8962		
	64.6 - 66.1m				Dry Basis	-	-	56.48	12.46	31.06	.44	9773		
58915	DDH 79-2	Raw Coal			Air Dried	-	6.93	42.54	32.04	18.49	.50	6873		
	112.2 - 113.0 m				Dry Basis	-	-	45.71	34.43	19.86	.54	7385		
58916	DDH 79-2	Raw Coal			Air Dried	-	4.54	27.95	58.31	9.20	.28	3760		
	117.95 - 119.05m				Dry Basis	-	-	29.28	61.08	9.64	.29	3939		

PLACER DEVELOPMENT LIMITED

ATTN: D. M. Jenkins

LORING LABORATORIES LTD.
CERTIFICATE of COAL TESTING

FILE N°.: 17457

DATE: August 8, 1979

Page # 3

[illegible]