



Loring Laboratories Ltd.

629 Beaverdam Road N.E.,

Calgary Alberta T2K 4W7

Tel: 274-2777 Fax: 275-0541

loringlabs@telus.net

TO: 1356139 ALBERTA INC.

291 SUNVALE DR. SE

Calgary, AB

Ph: 403-819-3944

File No : 5 0 5 9 4

Date : March 26, 2008

Samples : Drill Core

Attn: TOM KINNEY

Certificate of Assay

Sample No.	Au ppb
"Assay Analysis"	
11784	11
11785	8
11786	<5
11787	<5
11788	<5
11789	<5
11790	<5
11791	<5
11792	6
11793	<5
11794	<5
11795	<5
11796	<5
11797	13
11798	<5
11799	<5
11800	<5
11801	<5
11802	13
11803	<5
11804	19
11805	<5
11806	14
11807	<5
11808	<5

I HEREBY CERTIFY that the above results are those assays
made by me upon the herein described samples:

Assayer

Rejects and pulps are retained for one month unless specific arrangements are made in advance.



Loring Laboratories Ltd.

629 Beaverdam Road N.E.,
Calgary Alberta T2K 4W7
Tel: 274-2777 Fax: 275-0541
loringlabs@telus.net

TO: 1356139 Alberta Inc
291 Sunvale Dr. SE

FILE: 5 0 5 9 4

DATE: March 14, 2008

Attn: Tom Kinney

30 ELEMENT ICP ANALYSIS

Sample No.	Ag ppm	Al %	As ppm	Au ppm	B ppm	Ba ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P %	Pb ppm	Sb ppm	Sr ppm	Th ppm	Ti %	U ppm	V ppm	W ppm	Zn ppm
11784	1.9	0.23	3	<1	105	3	<1	0.31	4	100	1300	13	5.29	<0.01	<1	13.32	832	1	<0.01	2130	<0.01	<1	20	9	3	<0.01	<1	20	<1	3
11785	1.7	0.22	3	<1	101	2	<1	0.22	4	89	1130	13	4.90	<0.01	<1	12.52	750	1	<0.01	1810	<0.01	<1	14	9	1	<0.01	<1	18	<1	<1
11786	1.8	0.59	3	<1	73	3	<1	0.49	4	86	1550	1	4.47	<0.01	<1	12.18	615	2	<0.01	1660	<0.01	<1	24	7	9	<0.01	<1	30	<1	<1
11787	1.6	0.59	3	<1	91	3	<1	0.77	4	88	1930	22	4.62	<0.01	<1	12.48	699	1	<0.01	1850	<0.01	<1	30	11	13	<0.01	<1	35	<1	4
11788	1.6	0.64	5	<1	68	4	<1	0.86	4	87	1700	5	4.70	<0.01	1	11.92	685	1	<0.01	1700	<0.01	<1	23	14	9	<0.01	<1	30	<1	<1
11789	1.7	0.23	4	<1	125	2	<1	0.49	4	81	809	9	4.17	<0.01	<1	12.35	772	1	<0.01	1600	<0.01	<1	11	7	<1	<0.01	<1	17	<1	1
11790	1.5	0.18	4	<1	114	6	<1	0.83	4	85	700	6	4.38	<0.01	<1	11.94	878	<1	<0.01	1920	<0.01	2	9	11	<1	<0.01	<1	16	<1	<1
11791	1.8	0.23	4	<1	113	2	<1	0.46	4	92	1460	2	4.89	<0.01	<1	11.61	781	<1	<0.01	1700	<0.01	<1	22	7	11	<0.01	<1	25	<1	<1
11792	1.4	0.21	2	<1	131	2	<1	0.26	4	93	1180	9	4.96	<0.01	<1	12.68	648	1	<0.01	1780	<0.01	<1	19	6	<1	<0.01	<1	20	<1	<1
11793	1.6	0.18	4	<1	48	8	<1	0.25	3	85	841	4	4.03	<0.01	<1	12.76	519	2	<0.01	1810	<0.01	<1	13	33	3	<0.01	<1	13	<1	2
11794	1.9	0.23	5	<1	52	10	<1	0.25	4	97	1160	3	4.96	<0.01	<1	12.75	486	1	<0.01	1880	<0.01	<1	17	29	<1	<0.01	<1	19	<1	6
11795	1.4	0.29	3	<1	82	14	<1	1.05	4	79	1050	4	4.16	<0.01	<1	11.77	765	<1	<0.01	1520	<0.01	<1	16	131	3	<0.01	<1	20	<1	5
11796	1.5	0.30	4	<1	61	4	<1	0.66	3	72	808	4	3.64	<0.01	<1	9.91	486	17	<0.01	1330	<0.01	<1	12	40	2	<0.01	<1	15	<1	3
11797	1.5	0.25	3	<1	71	4	<1	0.27	4	82	1150	6	4.13	<0.01	<1	11.02	523	12	0.01	1620	<0.01	<1	18	18	3	<0.01	<1	16	<1	5
11798	1.4	0.19	5	<1	74	6	<1	1.12	3	76	1220	6	3.91	<0.01	3	10.24	643	3	0.01	1430	<0.01	<1	20	68	10	<0.01	<1	20	<1	5
11799	1.3	0.26	3	<1	67	6	<1	1.01	3	71	1130	7	3.57	<0.01	4	9.81	534	8	<0.01	1340	<0.01	<1	17	56	6	<0.01	<1	19	<1	4
11800	1.4	0.37	3	<1	53	11	<1	4.64	3	61	871	6	3.32	<0.01	17	9.25	633	19	<0.01	1190	<0.01	<1	11	281	3	<0.01	<1	17	<1	<1
11801	1.6	1.76	4	<1	36	42	<1	8.55	1	23	120	2	1.89	0.10	35	1.75	495	3	0.01	108	0.03	<1	2	389	<1	0.10	<1	76	<1	31
11802	1.2	1.22	6	<1	45	259	<1	5.90	1	16	57	111	1.22	0.04	25	0.86	153	3	0.01	37	0.03	<1	3	391	<1	0.11	<1	68	<1	43
11803	1.1	1.06	4	<1	44	167	<1	2.99	2	35	86	61	2.74	0.80	22	1.23	215	2	0.07	52	0.03	<1	5	181	<1	0.20	<1	100	<1	76
11804	1.5	1.38	9	<1	42	77	<1	2.99	3	49	106	75	4.42	0.96	20	1.93	523	1	0.08	60	0.03	<1	6	117	<1	0.23	<1	138	<1	87
11805	1.5	0.88	10	<1	45	65	<1	1.62	3	52	66	97	4.68	0.58	17	1.68	378	1	0.12	40	0.03	1	5	82	<1	0.13	<1	115	<1	75
11806	1.1	0.37	4	<1	44	41	<1	2.96	2	42	43	86	3.84	0.18	23	1.20	471	1	0.08	32	0.04	3	3	117	<1	0.03	<1	69	<1	59
11807	1.0	0.19	11	<1	39	41	<1	2.74	1	30	34	74	2.72	0.05	24	1.05	522	<1	0.04	30	0.04	6	8	94	<1	<0.01	<1	30	<1	46
11808	1.0	0.25	17	<1	33	45	<1	2.96	2	34	29	96	2.92	0.05	25	0.84	657	2	0.04	21	0.06	6	8	79	<1	<0.01	<1	38	<1	42
11809	0.6	0.33	15	<1	35	71	<1	0.78	1	32	30	87	2.56	0.04	22	0.69	438	2	0.07	20	0.07	9	13	35	<1	<0.01	<1	48	<1	57
11810	0.6	0.25	12	<1	33	98	<1	1.27	1	23	22	66	1.94	0.05	25	0.70	370	2	0.06	13	0.07	10	7	55	<1	<0.01	<1	28	<1	43
11811	0.9	0.21	20	<1	33	92	<1	2.41	2	23	36	55	1.83	0.04	26	0.97	404	4	0.04	20	0.06	8	12	104	<1	<0.01	<1	57	<1	59
11812	1.2	0.12	238	<1	31	19	<1	3.40	2	35	26	34	3.16	0.05	18	1.70	757	<1	0.06	28	<0.01	7	4	322	<1	<0.01	<1	19	<1	29
11813	1.6	0.15	221	<1	31	28	<1	3.57	2	39	18	52	3.63	0.06	20	1.75	688	1	0.05	29	0.01	9	4	320	<1	<0.01	<1	24	<1	52
11814	1.1	0.33	86	<1	31	37	<1	2.63	2	41	12	41	3.82	0.12	22	1.39	732	<1	0.04	13	0.08	5	4	220	<1	<0.01	<1	42	<1	49
11815	1.9	0.31	77	<1	31	29	<1	2.32	2	40	14	51	3.67	0.12	19	1.20	749	<1	0.05	11	0.04	6	3	150	<1	<0.01	<1	36	<1	47
11784R	1.9	0.22	3	<1	110	2	<1	0.33	4	104	1290	12	5.45	<0.01	<1	13.60	837	1	<0.01	2250	<0.01	<1	20	8	4	<0.01	<1	23	<1	4
11802R	1.1	1.35	5	<1	46	285	<1	6.10	1	18	62	113	1.30	0.05	28	0.90	160	4	0.01	39	0.03	<1	2	405	<1	0.12	<1	71	<1	45
blk	<0.5	<0.01	<1	<1	<1	<1	<1	<0.01	<1	<1	<1	<1	<0.01	<0.01	<1	<0.01	<1	<1	<0.01	<1	<0.01	<1	<1	<1	<1	<0.01	<1	<1	<1	<1

0.500 Gram sample is digested with Aqua Regia at 95 C for one hour and bulked to 10 ml with distilled water.
Partial dissolution for Al, B, Ba, Ca, Cr, Fe, K, La, Mg, Mn, Na, P, Sr, Ti, and W.

Certified by: _____