



Loring Laboratories Ltd.

629 Beaverdam Road N.E.,

Calgary Alberta T2K 4W7

Tel: 274-2777 Fax: 275-0541

loringlabs@telus.net

TO: 1356139 ALBERTA INC.

291 SUNVALE DR. SE

Calgary, AB

Ph: 403-819-3944

File No : 5 0 5 9 9

Date : March 26, 2008

Samples : Drill Core

Attn: TOM KINNEY

Certificate of Assay

| Sample No. | Au ppb |
|-------------------------|--------|
| "Assay Analysis" | |
| 11846 | 13 |
| 11847 | <5 |
| 11848 | <5 |
| 11849 | <5 |
| 11850 | <5 |
| 11851 | <5 |
| 11852 | <5 |
| 11853 | <5 |
| 11854 | 7 |
| 11855 | <5 |
| 11856 | <5 |
| 11857 | 9 |
| 11858 | <5 |
| 11859 | <5 |
| 11860 | 19 |
| 11861 | 7 |
| 11862 | <5 |
| 11863 | 11 |
| 11864 | <5 |
| 11865 | 18 |
| 11866 | 13 |
| 11867 | <5 |
| 11868 | 19 |
| 11869 | 435 |
| 11870 | 465 |

I HEREBY CERTIFY that the above results are those assays
made by me upon the herein described samples:

Assayer

Rejects and pulps are retained for one month unless specific arrangements are made in advance.



Loring Laboratories Ltd.

629 Beaverdam Road N.E.,
Calgary Alberta T2K 4W7
Tel: 274-2777 Fax: 275-0541
loringlabs@telus.net

TO: 1356139 Alberta Inc
291 Sunvale Dr. SE

FILE: 5 0 5 9 9

DATE: March 14, 2008

Attn: Tom Kinney

30 ELEMENT ICP ANALYSIS

| Sample No. | Ag ppm | Al % | As ppm | Au ppm | B ppm | Ba ppm | Bi ppm | Ca % | Cd ppm | Co ppm | Cr ppm | Cu ppm | Fe % | K % | La ppm | Mg % | Mn ppm | Mo ppm | Na % | Ni ppm | P % | Pb ppm | Sb ppm | Sr ppm | Th ppm | Ti % | U ppm | V ppm | W ppm | Zn ppm |
|------------|--------|-------|--------|--------|-------|--------|--------|-------|--------|--------|--------|--------|-------|-------|--------|-------|--------|--------|-------|--------|-------|--------|--------|--------|--------|-------|-------|-------|-------|--------|
| 11879 | 1.4 | 0.24 | 214 | <1 | <1 | 54 | <1 | 4.77 | 3 | 51 | 21 | 72 | 3.77 | 0.08 | 25 | 1.94 | 639 | 5 | 0.04 | 32 | 0.05 | 11 | 6 | 365 | <1 | <0.01 | <1 | 38 | <1 | 98 |
| 11880 | 1.5 | 0.30 | 127 | <1 | <1 | 33 | <1 | 4.92 | 3 | 54 | 14 | 62 | 3.91 | 0.08 | 26 | 1.76 | 675 | 6 | 0.04 | 30 | 0.12 | 15 | 8 | 394 | <1 | <0.01 | <1 | 40 | <1 | 126 |
| 11881 | 1.7 | 0.29 | 7 | <1 | 146 | 5 | <1 | 0.62 | 5 | 114 | 979 | 14 | 4.64 | <0.01 | <1 | 14.93 | 624 | 2 | <0.01 | 2000 | <0.01 | <1 | 21 | 29 | <1 | <0.01 | <1 | 25 | <1 | 15 |
| 11882 | 1.7 | 0.24 | 4 | <1 | 152 | 8 | <1 | 0.44 | 5 | 116 | 1310 | 8 | 5.17 | <0.01 | <1 | 14.56 | 644 | 2 | <0.01 | 2210 | <0.01 | <1 | 26 | 20 | 4 | <0.01 | <1 | 28 | <1 | 8 |
| 11883 | 1.6 | 0.23 | 3 | <1 | 137 | 3 | <1 | 0.42 | 5 | 101 | 1100 | 5 | 4.84 | <0.01 | <1 | 14.16 | 585 | 2 | <0.01 | 1910 | <0.01 | <1 | 23 | 19 | 9 | <0.01 | <1 | 26 | <1 | 6 |
| 11884 | 2.2 | 0.25 | 4 | <1 | 157 | 3 | <1 | 0.19 | 5 | 105 | 1180 | 9 | 4.91 | <0.01 | <1 | 14.95 | 705 | 2 | <0.01 | 2000 | <0.01 | <1 | 22 | 7 | 2 | <0.01 | <1 | 24 | <1 | 9 |
| 11885 | 2.0 | 0.21 | 3 | <1 | 151 | 3 | <1 | 0.51 | 5 | 108 | 1140 | 7 | 5.29 | <0.01 | <1 | 14.60 | 776 | 2 | <0.01 | 2040 | <0.01 | <1 | 21 | 15 | 3 | <0.01 | <1 | 25 | <1 | 6 |
| 11886 | 1.9 | 0.27 | 4 | <1 | 149 | 2 | <1 | 0.07 | 5 | 120 | 1510 | 6 | 5.63 | <0.01 | <1 | 14.70 | 721 | 2 | <0.01 | 2380 | <0.01 | <1 | 26 | 6 | 9 | <0.01 | <1 | 28 | <1 | 6 |
| 11887 | 1.8 | 0.26 | 2 | <1 | 138 | 2 | <1 | 0.15 | 5 | 106 | 1380 | 6 | 5.11 | <0.01 | <1 | 14.68 | 703 | 2 | <0.01 | 1960 | <0.01 | <1 | 25 | 7 | 5 | <0.01 | <1 | 24 | <1 | 5 |
| 11888 | 1.6 | 0.25 | 4 | <1 | 159 | 2 | <1 | 0.25 | 6 | 117 | 1380 | 9 | 5.73 | <0.01 | <1 | 14.84 | 788 | 2 | <0.01 | 2250 | <0.01 | <1 | 25 | 9 | 7 | <0.01 | <1 | 26 | <1 | 5 |
| 11889 | 2.0 | 0.24 | 3 | <1 | 161 | 2 | <1 | 0.15 | 5 | 118 | 1050 | 5 | 5.26 | <0.01 | <1 | 14.60 | 650 | 2 | <0.01 | 2170 | <0.01 | <1 | 19 | 8 | 3 | <0.01 | <1 | 23 | <1 | 5 |
| 11890 | 1.9 | 0.33 | 3 | <1 | 151 | 2 | <1 | 0.25 | 5 | 111 | 1280 | 5 | 5.57 | <0.01 | <1 | 14.77 | 720 | 2 | <0.01 | 1990 | <0.01 | <1 | 21 | 7 | 4 | <0.01 | <1 | 26 | <1 | 4 |
| 11891 | 1.8 | 0.25 | 4 | <1 | 152 | 2 | <1 | 0.48 | 5 | 106 | 1120 | 5 | 4.98 | <0.01 | <1 | 14.75 | 721 | 2 | <0.01 | 1980 | <0.01 | <1 | 19 | 9 | 8 | <0.01 | <1 | 23 | <1 | 4 |
| 11892 | 1.8 | 0.28 | 2 | <1 | 168 | 2 | <1 | 0.14 | 5 | 112 | 1070 | 2 | 5.56 | <0.01 | <1 | 15.19 | 707 | 2 | <0.01 | 2140 | <0.01 | 1 | 20 | 6 | 2 | <0.01 | <1 | 26 | <1 | 5 |
| 11893 | 1.3 | 0.21 | 4 | <1 | 50 | 11 | <1 | 0.59 | 4 | 95 | 1010 | 6 | 3.84 | <0.01 | <1 | 11.57 | 521 | 56 | 0.01 | 1840 | <0.01 | <1 | 20 | 62 | 4 | <0.01 | <1 | 20 | <1 | 12 |
| 11894 | 1.4 | 0.31 | 4 | <1 | 25 | 16 | <1 | 0.86 | 4 | 88 | 897 | 5 | 3.83 | <0.01 | <1 | 11.22 | 510 | 76 | <0.01 | 1690 | <0.01 | <1 | 16 | 88 | 7 | <0.01 | <1 | 19 | <1 | 12 |
| 11895 | 1.4 | 0.23 | 5 | <1 | 54 | 11 | <1 | 0.13 | 4 | 108 | 966 | 7 | 4.02 | <0.01 | <1 | 11.88 | 485 | 95 | <0.01 | 2130 | <0.01 | <1 | 19 | 26 | 12 | <0.01 | <1 | 21 | <1 | 12 |
| 11896 | 1.6 | 0.40 | 3 | <1 | 41 | 5 | <1 | 0.09 | 4 | 96 | 1480 | 7 | 4.34 | <0.01 | <1 | 12.50 | 473 | 31 | <0.01 | 1680 | <0.01 | <1 | 30 | 25 | 8 | <0.01 | <1 | 29 | <1 | 13 |
| 11897 | 1.2 | 0.27 | 3 | <1 | 14 | 12 | <1 | 2.55 | 3 | 63 | 763 | 7 | 2.39 | <0.01 | 12 | 7.47 | 383 | 45 | <0.01 | 1170 | <0.01 | <1 | 15 | 228 | 3 | <0.01 | <1 | 17 | <1 | 3 |
| 11898 | 1.0 | 0.51 | 4 | <1 | <1 | 20 | <1 | 5.20 | 2 | 40 | 503 | 2 | 1.28 | <0.01 | 21 | 4.27 | 319 | 43 | <0.01 | 806 | <0.01 | <1 | 13 | 545 | 10 | <0.01 | <1 | 12 | <1 | <1 |
| 11899 | 1.0 | 0.10 | 2 | <1 | <1 | 63 | <1 | 6.83 | <1 | 6 | 35 | 1 | 0.27 | <0.01 | 33 | 0.88 | 159 | 3 | <0.01 | 74 | 0.06 | <1 | 1 | 1260 | 3 | 0.04 | <1 | 13 | <1 | <1 |
| 11900 | 1.6 | 0.56 | 5 | <1 | <1 | 64 | <1 | 11.20 | <1 | 31 | 146 | 4 | 0.77 | 0.32 | 38 | 1.36 | 205 | 61 | <0.01 | 715 | <0.01 | <1 | 14 | 1410 | <1 | 0.01 | <1 | 13 | <1 | <1 |
| 11901 | 1.3 | 0.17 | 6 | <1 | <1 | 125 | <1 | 9.52 | <1 | 19 | 41 | 41 | 0.99 | 0.05 | 38 | 0.52 | 218 | 15 | 0.03 | 198 | 0.04 | 2 | 13 | 932 | 4 | 0.06 | <1 | 30 | <1 | 22 |
| 11902 | 1.1 | 0.14 | 1 | <1 | <1 | 47 | <1 | 4.18 | <1 | 10 | 21 | 108 | 0.62 | 0.03 | 31 | 0.26 | 152 | 2 | 0.06 | 16 | 0.08 | 5 | 2 | 268 | 6 | 0.13 | <1 | 29 | <1 | 23 |
| 11903 | 1.4 | 0.30 | 3 | <1 | <1 | 139 | <1 | 9.54 | <1 | 5 | 12 | 179 | 0.41 | 0.16 | 39 | 0.70 | 150 | 3 | 0.01 | 10 | 0.05 | 3 | <1 | 882 | 2 | 0.07 | <1 | 18 | <1 | <1 |
| 11904 | 1.1 | 0.22 | 4 | <1 | <1 | 252 | <1 | 7.63 | <1 | 3 | 12 | 5 | 0.27 | 0.06 | 33 | 0.89 | 130 | 2 | 0.02 | 5 | 0.06 | 9 | <1 | 743 | 2 | 0.07 | <1 | 17 | <1 | <1 |
| 11905 | 0.9 | 1.32 | 3 | <1 | <1 | 73 | <1 | 6.56 | <1 | 9 | 21 | 5 | 0.71 | 0.41 | 28 | 2.52 | 252 | 2 | 0.02 | 14 | 0.05 | <1 | <1 | 562 | 3 | 0.09 | <1 | 23 | <1 | 15 |
| 11906 | 1.3 | 0.26 | 3 | <1 | <1 | 179 | <1 | 9.34 | <1 | 5 | 12 | 29 | 0.33 | 0.11 | 39 | 0.78 | 113 | 2 | 0.01 | 10 | 0.05 | 4 | <1 | 1190 | 3 | 0.06 | <1 | 19 | <1 | 7 |
| 11907 | 1.2 | 0.93 | 10 | <1 | 9 | 170 | <1 | 7.73 | <1 | 24 | 113 | 18 | 0.80 | 0.71 | 32 | 1.94 | 150 | 2 | 0.02 | 426 | 0.03 | <1 | 39 | 721 | 2 | 0.04 | <1 | 15 | <1 | 8 |
| 11882R | 1.8 | 0.27 | 3 | <1 | 150 | 7 | <1 | 0.41 | 5 | 111 | 1320 | 9 | 5.42 | <0.01 | <1 | 14.34 | 680 | 2 | <0.01 | 2230 | <0.01 | <1 | 23 | 20 | 3 | <0.01 | <1 | 26 | <1 | 6 |
| 11900R | 1.6 | 0.56 | 5 | <1 | <1 | 64 | <1 | 11.22 | <1 | 32 | 154 | 3 | 0.79 | 0.31 | 39 | 1.39 | 211 | 64 | <0.01 | 731 | <0.01 | <1 | 14 | 1430 | 1 | 0.01 | <1 | 12 | <1 | <1 |
| blk | <0.5 | <0.01 | <1 | <1 | <1 | <1 | <1 | <0.01 | <1 | <1 | <1 | <1 | <0.01 | <0.01 | <1 | <0.01 | <1 | <1 | <0.01 | <1 | <0.01 | <1 | <1 | <1 | <1 | <0.01 | <1 | <1 | <1 | <1 |

0.500 Gram sample is digested with Aqua Regia at 95 C for one hour and bulked to 10 ml with distilled water.
Partial dissolution for Al, B, Ba, Ca, Cr, Fe, K, La, Mg, Mn, Na, P, Sr, Ti, and W.

Certified by: _____



Loring Laboratories Ltd.

629 Beaverdam Road N.E.,
Calgary Alberta T2K 4W7
Tel: 274-2777 Fax: 275-0541
loringlabs@telus.net

TO: 1356139 Alberta Inc
291 Sunvale Dr. SE

FILE: 5 1 0 3 4

DATE: Aug. 7, 2008

Attn: Tom Kinney

30 ELEMENT ICP ANALYSIS

| Sample No. | Ag ppm | Al % | As ppm | Au ppb | B ppm | Ba ppm | Bi ppm | Ca % | Cd ppm | Co ppm | Cr ppm | Cu ppm | Fe % | K % | La ppm | Mg % | Mn ppm | Mo ppm | Na % | Ni ppm | P % | Pb ppm | Sb ppm | Sr ppm | Th ppm | Ti % | U ppm | V ppm | W ppm | Zn ppm |
|-------------|--------|------|--------|--------|-------|--------|--------|------|--------|--------|--------|--------|------|------|--------|------|--------|--------|------|--------|------|--------|--------|--------|--------|-------|-------|-------|-------|--------|
| 11914 | <0.5 | 0.55 | 15 | <5 | <1 | 36 | <1 | 2.86 | 2 | 38 | 27 | 44 | 3.36 | 0.10 | 23 | 1.11 | 744 | <1 | 0.04 | 18 | 0.08 | 51 | 2 | 166 | <1 | <0.01 | <1 | 46 | <1 | 50 |
| 11915 | <0.5 | 1.18 | 15 | <5 | <1 | 39 | <1 | 2.52 | 3 | 45 | 36 | 61 | 4.13 | 0.05 | 25 | 1.31 | 665 | 2 | 0.04 | 22 | 0.08 | 18 | 3 | 132 | <1 | <0.01 | <1 | 104 | <1 | 62 |
| 11916 | <0.5 | 1.29 | 9 | <5 | <1 | 31 | <1 | 3.73 | 3 | 42 | 24 | 47 | 4.06 | 0.04 | 25 | 1.04 | 868 | 2 | 0.03 | 12 | 0.09 | 12 | 1 | 52 | <1 | 0.15 | <1 | 86 | <1 | 53 |
| 11917 | <0.5 | 1.71 | 9 | <5 | <1 | 23 | <1 | 2.47 | 3 | 46 | 24 | 60 | 4.41 | 0.04 | 24 | 1.14 | 705 | 2 | 0.03 | 13 | 0.09 | 27 | 3 | 38 | <1 | 0.17 | <1 | 93 | <1 | 69 |
| 11918 | <0.5 | 1.07 | 7 | <5 | 13 | 19 | <1 | 6.90 | 2 | 30 | 17 | 44 | 2.78 | 0.03 | 31 | 0.73 | 756 | 2 | 0.02 | 6 | 0.08 | 13 | 1 | 160 | <1 | 0.11 | <1 | 64 | <1 | 37 |
| 11919 | <0.5 | 1.04 | 12 | <5 | <1 | 16 | <1 | 6.69 | 2 | 35 | 32 | 235 | 3.25 | 0.03 | 31 | 0.83 | 830 | 2 | 0.02 | 13 | 0.08 | 14 | 2 | 108 | <1 | 0.11 | <1 | 67 | <1 | 39 |
| 11914 check | <0.5 | 0.58 | 16 | <5 | <1 | 38 | <1 | 2.95 | 2 | 39 | 27 | 43 | 3.33 | 0.10 | 24 | 1.14 | 741 | 1 | 0.04 | 19 | 0.09 | 49 | 2 | 168 | <1 | <0.01 | <1 | 46 | <1 | 52 |

0.500 Gram sample is digested with Aqua Regia at 95 C for one hour and bulked to 10 ml with distilled water.
Partial dissolution for Al, B, Ba, Ca, Cr, Fe, K, La, Mg, Mn, Na, P, Sr, Ti, and W.

Gold analyzed using 30 grams fusion Fire Assay with AA finish.

Certified by: _____