



Loring Laboratories Ltd.

629 Beaverdam Road N.E.,
Calgary Alberta T2K 4W7
Tel: 274-2777 Fax: 275-0541
loringlabs@telus.net

TO: 1356139 ALBERTA INC.
291 SUNVALE DR. SE
Calgary, AB
Ph: 403-819-3944

File No : 5 0 5 6 8
Date : March 26, 2008
Samples : Drill Core

Attn: TOM KINNEY

Certificate of Assay

Sample No.	Au ppb
"Assay Analysis"	
11776	<5
11777	58
11778	<5
11779	22
11780	56
11781	17
11782	18
11783	19

I HEREBY CERTIFY that the above results are those assays
made by me upon the herein described samples:

Assayer

Sects and pulps are retained for one month unless specific arrangements are made in advance.



Loring Laboratories Ltd.

629 Beaverdam Road N.E.,
Calgary Alberta T2K 4W7
Tel: 274-2777 Fax: 275-0541
loringlabs@telus.net

TO: 1356139 Alberta Inc
291 Sunvale Dr. SE

FILE: 5 0 5 6 8

DATE: March 11, 2008

Attn: Tom Kinney

30 ELEMENT ICP ANALYSIS

Sample No.	Ag ppm	Al %	As ppm	Au ppm	B ppm	Ba ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P %	Pb ppm	Sb ppm	Sr ppm	Th ppm	Ti %	U ppm	V ppm	W ppm	Zn ppm
011751	2.2	0.41	11	<1	64	10	<1	1.38	5	87	1720	12	4.93	<0.01	2	12.89	889	1	<0.01	1740	<0.01	<1	23	57	4	<0.01	<1	34	<1	9
011752	2.2	0.43	14	<1	64	11	<1	2.09	5	96	1940	35	4.99	<0.01	3	13.18	1098	1	<0.01	1970	<0.01	<1	27	103	8	<0.01	<1	36	<1	6
011753	2.2	0.29	11	<1	76	14	<1	1.37	5	104	1600	4	5.11	<0.01	<1	13.11	657	1	<0.01	2120	<0.01	<1	22	90	<1	<0.01	<1	28	<1	5
011754	2.6	0.35	10	<1	56	60	<1	4.82	4	89	1470	5	4.23	<0.01	14	11.13	860	1	<0.01	1810	<0.01	<1	21	400	10	<0.01	<1	32	<1	6
011755	2.5	2.54	33	<1	10	171	<1	5.93	5	69	694	60	4.82	0.02	20	7.99	1190	2	<0.01	715	0.04	<1	15	629	<1	<0.01	<1	123	<1	25
011756	2.7	3.18	73	<1	7	238	<1	5.08	6	75	266	56	7.09	0.04	21	7.70	1193	2	<0.01	352	0.04	<1	7	662	<1	<0.01	<1	192	<1	48
011757	2.2	0.08	281	<1	16	63	<1	2.10	4	70	339	6	4.06	0.01	6	10.65	652	1	<0.01	1450	<0.01	2	24	201	<1	<0.01	<1	16	<1	<1
011758	2.1	0.09	245	<1	14	52	<1	2.28	4	72	329	5	3.85	0.01	9	10.44	596	<1	<0.01	1470	<0.01	2	32	240	<1	<0.01	<1	16	<1	<1
011759	2.4	0.08	295	<1	<1	82	<1	5.97	4	50	259	27	3.47	0.03	22	8.54	695	<1	<0.01	744	<0.01	2	38	925	<1	<0.01	<1	26	<1	<1
011760	2.1	0.17	272	<1	<1	26	<1	1.26	4	73	882	9	3.79	0.01	4	10.11	661	1	<0.01	1370	<0.01	<1	18	123	1	<0.01	<1	21	<1	<1
011761	1.4	0.12	255	<1	10	25	<1	0.47	4	69	568	5	3.62	<0.01	<1	10.66	587	1	<0.01	1390	<0.01	<1	19	39	<1	<0.01	<1	14	<1	<1
011762	1.9	0.10	356	<1	10	16	<1	0.50	4	74	614	6	3.66	0.01	<1	10.26	647	1	<0.01	1320	<0.01	1	30	32	<1	<0.01	<1	14	<1	<1
011763	2.4	0.03	430	<1	12	31	<1	0.81	5	78	431	8	4.49	0.01	<1	12.08	777	1	<0.01	1570	<0.01	2	42	70	<1	<0.01	<1	15	<1	<1
011764	1.9	0.02	505	<1	11	14	<1	0.53	4	62	290	5	3.39	0.01	<1	10.07	583	1	<0.01	1150	<0.01	1	42	49	<1	<0.01	<1	15	<1	<1
011765	2.3	0.03	247	<1	8	26	<1	2.21	4	66	280	5	3.74	0.02	6	10.15	705	1	<0.01	1210	<0.01	3	31	231	<1	<0.01	<1	16	<1	<1
011766	2.2	0.02	1210	<1	9	21	<1	1.22	4	82	251	5	4.04	0.02	3	10.48	618	1	<0.01	1470	<0.01	3	65	164	<1	<0.01	<1	15	<1	5
011767	2.2	0.02	1140	<1	7	16	<1	0.43	4	72	213	3	3.64	0.01	<1	10.35	566	1	<0.01	1260	<0.01	2	57	69	<1	<0.01	<1	16	<1	2
011768	2.3	0.07	1370	<1	8	48	<1	2.00	4	67	202	8	3.74	0.04	9	9.46	641	<1	0.01	1040	<0.01	4	51	377	<1	<0.01	<1	18	<1	6
011769	1.9	0.34	150	<1	<1	42	<1	2.77	3	39	21	77	3.28	0.06	19	2.25	469	1	0.03	60	0.02	10	12	407	4	<0.01	<1	14	<1	65
011770	1.3	0.42	115	<1	<1	49	<1	3.27	3	42	24	66	3.63	0.12	21	1.78	725	<1	0.02	29	0.07	10	7	300	<1	<0.01	<1	13	<1	69
011771	1.1	0.32	45	<1	10	67	<1	3.20	3	39	21	50	3.22	0.16	24	1.60	754	<1	0.02	22	0.06	7	4	362	<1	<0.01	<1	17	<1	67
011772	1.0	0.42	24	<1	19	73	<1	1.93	3	46	16	80	3.79	0.19	21	1.60	624	<1	0.03	32	0.08	11	4	201	<1	<0.01	<1	22	<1	85
011773	1.2	0.35	99	<1	9	50	<1	2.51	2	39	24	72	3.09	0.15	20	1.35	582	<1	0.02	23	0.09	9	5	303	<1	<0.01	<1	15	<1	73
011774	1.7	0.35	116	<1	11	53	<1	2.00	3	46	16	131	3.78	0.17	17	1.53	601	<1	0.03	30	0.06	10	4	315	<1	<0.01	<1	14	<1	97
011775	1.1	0.64	39	<1	16	82	<1	3.56	3	38	44	48	3.17	0.10	23	1.76	928	5	0.04	24	0.08	8	4	171	<1	<0.01	<1	38	<1	65
011776	1.0	0.65	14	<1	13	100	<1	2.47	2	34	44	50	2.63	0.11	22	1.17	574	<1	0.03	26	0.08	6	4	132	<1	<0.01	<1	42	<1	57
011777	1.3	1.09	14	<1	12	145	<1	2.78	3	42	50	69	3.23	0.09	23	1.52	640	1	0.03	27	0.09	2	2	101	<1	<0.01	<1	67	<1	78
011778	1.2	0.44	34	<1	4	72	<1	3.38	3	48	4	85	3.94	0.15	18	1.57	682	2	<0.01	30	0.08	9	6	261	<1	<0.01	<1	16	<1	90
011779	1.1	0.51	31	<1	<1	64	<1	3.09	3	44	5	66	3.66	0.14	20	1.60	692	1	0.01	22	0.09	8	4	179	<1	<0.01	<1	19	<1	79
011780	1.4	0.53	16	<1	<1	226	<1	3.83	4	54	22	87	4.87	0.10	22	1.23	985	2	0.03	14	0.11	11	4	106	<1	<0.01	<1	72	<1	77
011781	1.8	0.63	13	<1	14	136	<1	8.33	3	42	23	36	3.98	0.10	37	1.21	1117	2	0.03	13	0.09	4	3	242	<1	<0.01	<1	61	<1	48
011782	1.7	1.25	12	<1	18	153	<1	5.54	3	46	31	58	4.23	0.06	34	1.18	1112	1	0.05	12	0.11	<1	4	116	<1	0.06	<1	95	<1	56
011783	1.5	1.44	15	<1	21	188	<1	3.56	3	48	59	40	4.27	0.06	22	1.22	826	2	0.04	13	0.09	<1	3	66	<1	0.15	<1	107	<1	67
011761 chk	1.6	0.10	258	<1	9	26	<1	0.47	4	69	552	5	3.30	<0.01	<1	10.41	558	1	<0.01	1380	<0.01	<1	18	39	<1	<0.01	<1	13	<1	<1
blk	<0.5	<0.01	<1	<1	<1	<1	<1	<0.01	<1	<1	<1	<1	<0.01	<0.01	<1	<0.01	<1	<1	<0.01	<1	<0.01	<1	<1	<1	<1	<0.01	<1	<1	<1	<1

0.500 Gram sample is digested with Aqua Regia at 95 C for one hour and bulked to 10 ml with distilled water.
Partial dissolution for Al, B, Ba, Ca, Cr, Fe, K, La, Mg, Mn, Na, P, Sr, Ti, and W.

Certified by: _____