



Loring Laboratories Ltd.

629 Beaverdam Road N.E.,
Calgary Alberta T2K 4W7
Tel: 274-2777 Fax: 275-0541
loringlabs@telus.net

TO: 1356139 Alberta Inc
291 Sunvale Dr. SE

FILE: 5 0 7 7 2

DATE: May 11, 2008

Attn: Tom Kinney

30 ELEMENT ICP ANALYSIS

Sample No.	Ag ppm	Al %	As ppm	Au ppb	B ppm	Ba ppm	Bi ppm	Ca %	Cd ppm	Co ppm	Cr ppm	Cu ppm	Fe %	K %	La ppm	Mg %	Mn ppm	Mo ppm	Na %	Ni ppm	P %	Pb ppm	Sb ppm	Sr ppm	Th ppm	Ti %	U ppm	V ppm	W ppm	Zn ppm
11908	<0.5	0.18	8	30	179	5	<1	0.07	4	111	1170	7	4.65	<0.01	<1	13.01	716	2	<0.01	1940	<0.01	<1	26	10	<1	<0.01	<1	23	<1	14
11909	<0.5	0.17	8	<5	119	5	<1	0.20	4	111	1220	9	4.89	<0.01	<1	13.05	621	2	<0.01	1990	<0.01	<1	24	33	<1	<0.01	<1	25	<1	14
11910	<0.5	0.16	8	10	196	6	<1	0.34	4	109	1030	8	4.64	<0.01	<1	13.34	838	2	<0.01	1890	<0.01	<1	23	44	<1	<0.01	<1	24	<1	9
11911	<0.5	0.14	7	<5	128	8	<1	0.37	4	109	1020	10	4.83	<0.01	<1	13.40	730	1	<0.01	1900	<0.01	<1	24	53	<1	<0.01	<1	25	<1	11
11912	<0.5	0.15	7	28	122	6	<1	0.09	4	109	1150	15	4.74	<0.01	<1	13.25	711	2	<0.01	1920	<0.01	<1	28	16	<1	<0.01	<1	26	<1	12
11913	<0.5	0.15	8	<5	119	6	<1	0.28	4	112	1130	18	4.85	<0.01	<1	13.29	555	2	<0.01	1960	<0.01	<1	27	43	<1	<0.01	<1	23	<1	12
11908 chk	<0.5	0.16	6	<5	177	5	<1	0.06	4	107	1100	6	4.56	<0.01	<1	12.98	695	2	<0.01	1920	<0.01	<1	26	10	<1	<0.01	<1	22	<1	12

0.500 Gram sample is digested with Aqua Regia at 95 C for one hour and bulked to 10 ml with distilled water.
Partial dissolution for Al, B, Ba, Ca, Cr, Fe, K, La, Mg, Mn, Na, P, Sr, Ti, and W.

Gold analyzed using 30 grams fusion Fire Assay with AA finish.

Certified by: _____