

SAMPLE#	MO PPM	CU PPM	PB PPM	ZN PPM	AG PPM	NI PPM	CO PPM	MM PPM	FE %	AS PPM	U PPM	AU PPM	TH PPM	SA PPM	CD PPM	SB PPM	BI PPM	V PPM	CA %	P %	LA PPM	CR PPM	MG %	BA PPM	TI %	B PPM	AL %	NA %	K %	H PPM	AU PPM
6H-07-06 155-156M	1	2	2	5	.1	5	1	64	.20	3	5	ND	1	268	1	2	3	11	32.36	.011	2	3	3.45	13	.01	9	.02	.01	.01	1	1
6H-07-06 157-158M	1	2	2	7	.1	4	1	70	.22	3	5	ND	1	187	1	2	4	13	33.07	.006	2	4	4.47	6	.01	2	.01	.01	.01	1	2
6H-07-06 159-160M	1	1	3	3	.1	2	1	46	.15	4	5	ND	1	197	1	2	2	12	34.46	.006	2	3	3.32	6	.01	6	.01	.01	.01	1	1
6H-07-06 161-162M	1	2	5	6	.2	4	1	44	.20	2	5	ND	1	371	1	2	2	5	35.03	.009	2	4	2.37	5	.01	5	.04	.01	.02	1	2
6H-07-07 11-12M	1	108	11	108	.3	79	20	487	5.14	5	5	ND	10	70	1	2	2	21	2.74	.057	24	43	1.49	30	.01	2	2.08	.03	.12	2	1
6H-07-07 13-14M	2	57	11	104	.3	56	13	719	4.36	6	5	ND	14	91	1	2	2	18	4.91	.061	32	35	1.71	21	.01	2	1.66	.02	.09	4	2
6H-07-07 15-16M	1	98	12	105	.3	80	19	373	4.91	5	5	ND	10	42	1	2	2	25	1.34	.072	21	30	1.53	25	.01	2	2.01	.04	.09	2	2
6H-07-07 17-18M	1	51	10	157	.3	75	18	483	6.27	2	5	ND	10	44	1	2	2	38	1.63	.076	32	67	2.24	23	.01	2	3.04	.04	.08	1	1
6H-07-07 21-22M	2	87	11	140	.4	85	21	193	6.13	5	5	ND	12	42	1	2	2	34	.49	.069	31	65	1.90	25	.01	2	2.85	.04	.10	1	2
6H-07-07 25-26M	1	55	10	80	.4	79	18	822	4.23	4	5	ND	8	106	1	2	2	14	3.88	.061	21	34	1.42	30	.01	2	1.05	.03	.14	2	2
6H-07-07 27-28M	2	56	10	110	.3	72	17	728	5.27	5	5	ND	8	98	1	2	2	20	3.61	.058	20	32	1.58	22	.01	2	1.48	.03	.10	1	1
6H-07-07 29-30M	2	54	6	121	.3	76	18	1125	5.05	7	5	ND	9	143	1	2	2	15	5.00	.064	27	24	1.94	25	.01	2	1.36	.02	.12	2	2
6H-07-07 31-32M	2	41	11	141	.3	83	17	474	4.52	5	5	ND	7	138	1	2	2	24	3.42	.064	13	59	1.58	20	.01	2	1.74	.03	.09	1	1
6H-07-07 33.3-33.7M	3	164	7	130	.8	67	17	456	6.64	7	5	ND	6	118	1	2	2	3	4.31	.062	4	3	.13	16	.01	4	.21	.04	.07	1	2
6H-07-07 35-36M	1	109	7	52	.5	69	16	836	4.63	4	5	ND	6	213	1	2	2	6	5.09	.086	10	8	1.71	24	.01	5	.41	.03	.11	1	1
6H-07-07 37-38M	2	254	8	32	.6	52	19	477	5.71	6	5	ND	7	156	1	2	2	5	4.03	.070	17	5	.60	25	.01	2	.25	.05	.11	2	2
6H-07-07 39-40M	39	66	4	349	.4	62	2	441	.99	2	5	ND	2	884	4	2	2	19	22.72	.033	8	1	.51	15	.01	2	.11	.01	.05	1	1
6H-07-07 41-42M	23	92	7	1361	.7	78	8	264	.94	4	5	ND	5	566	17	2	2	82	16.90	.091	10	18	.58	31	.01	2	.24	.01	.09	2	8
6H-07-07 43-44M	27	48	2	995	.4	38	1	415	.88	2	5	ND	2	832	18	2	2	46	19.93	.032	8	4	2.94	13	.01	11	.09	.01	.05	2	2
6H-07-07 47-52M	15	14	6	497	.3	37	3	285	1.34	13	5	ND	2	414	6	2	2	16	19.63	.042	6	1	.68	28	.01	2	.19	.01	.06	1	1
6H-07-07 53-54M	19	19	4	330	.4	35	2	193	1.03	19	5	ND	2	387	4	2	2	21	21.56	.025	5	3	.62	16	.01	5	.10	.01	.05	1	2
6H-07-07 55-56M	13	10	4	207	.3	47	3	156	1.08	19	5	ND	3	392	2	2	2	15	22.64	.020	5	1	.77	16	.01	2	.09	.01	.03	1	1
6H-07-07 57-58M	27	20	10	277	.4	80	5	142	1.63	31	5	ND	3	195	3	2	2	13	13.18	.019	3	1	.94	19	.08	2	.13	.01	.04	1	1
6H-07-07 59-62M	13	14	3	168	.5	41	3	235	1.09	16	5	ND	3	485	2	2	2	11	22.65	.017	2	1	.95	16	.01	5	.10	.01	.04	1	2
6H-07-07 63-64M	26	22	13	180	.7	63	7	213	2.13	46	5	ND	4	202	2	2	2	12	13.58	.025	3	4	.92	19	.01	2	.17	.01	.06	1	4
6H-07-07 65-66M	22	21	6	245	.6	44	4	315	1.43	22	5	ND	2	358	3	2	2	8	21.17	.023	4	3	1.38	15	.01	2	.10	.01	.04	1	2
6H-07-07 67-68M	23	9	3	130	.5	29	1	170	.58	15	5	ND	1	530	3	2	3	18	26.67	.023	4	3	.27	53	.01	2	.05	.01	.02	1	1
6H-07-07 69-70M	27	22	2	158	.4	76	2	188	.95	61	5	ND	1	316	3	2	2	26	22.19	.026	7	1	1.87	5	.01	2	.06	.01	.02	1	1
6H-07-07 71-72M	23	32	2	275	.5	77	1	99	.64	67	5	ND	1	426	2	2	2	28	26.48	.021	5	6	1.21	5	.01	7	.04	.01	.01	1	2
6H-07-07 73-74M	17	23	2	137	.5	53	1	129	.58	38	5	ND	1	441	1	2	2	26	30.18	.019	4	3	1.59	3	.01	8	.03	.01	.02	1	1
6H-07-07 75-76M	25	46	3	332	.6	78	2	96	.72	41	5	ND	1	300	4	2	2	46	20.66	.083	5	4	.66	6	.01	19	.08	.01	.03	1	2
6H-07-07 77-78M	3	33	2	147	.5	39	1	133	.63	17	5	ND	1	312	1	2	2	17	21.20	.195	6	8	1.78	5	.01	14	.08	.01	.03	1	1
6H-07-07 79-80M	2	47	4	118	.7	59	3	139	.83	33	5	ND	1	233	2	2	2	16	14.76	.257	6	9	1.86	8	.01	2	.13	.01	.06	1	2
6H-07-07 81-82M	1	34	4	96	.6	41	2	154	.79	26	5	ND	1	296	1	2	2	7	19.61	.112	4	4	1.44	5	.01	2	.09	.01	.04	1	2
6H-07-07 83-84M	3	47	5	153	.6	48	2	123	.81	29	5	ND	1	217	2	2	2	11	13.72	.162	4	7	.79	6	.01	14	.10	.01	.05	1	1
6H-07-07 85-86M	5	36	5	208	.5	62	14	148	1.90	27	5	ND	2	178	2	2	2	15	11.44	.165	3	5	.33	19	.01	2	.31	.01	.15	1	4
STD C/AU-R	18	57	38	128	7.3	66	27	1032	3.85	40	15	7	39	50	18	17	19	57	.42	.086	38	60	.85	179	.08	37	1.78	.08	.14	13	500

STRYKER FREEPORT FILE # 87-3791

Page 4

SAMPLE#	NO	CU	PB	ZN	AG	NI	CO	MM	FE	AS	U	AU	TH	SR	CD	SB	BI	V	CA	P	LA	CR	MG	BA	TI	B	AL	MA	K	#	AU#
	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM
6H-87-07 86.1-86.2M	6	54	5	185	.3	81	15	316	3.05	29	5	ND	1	207	1	2	4	7	17.11	.173	3	19	3.72	11	.01	16	.22	.01	.09	1	1
6H-87-07 86.2-87M	5	8	3	55	.5	19	1	247	.56	11	6	ND	1	332	1	4	7	4	32.30	.041	4	1	3.95	5	.01	2	.03	.01	.01	1	1
6H-87-07 87-88M	4	4	2	34	.4	14	1	148	.40	14	5	ND	1	339	1	5	4	8	30.78	.022	2	3	3.48	5	.01	6	.01	.01	.01	1	1
6H-87-07 89-90M	1	2	4	4	.4	4	1	48	.15	2	5	ND	1	207	1	3	7	4	35.46	.004	2	1	3.48	3	.01	2	.01	.01	.01	1	1
6H-87-07 91-92M	1	5	3	4	.2	5	1	109	.24	3	5	ND	1	232	1	2	7	3	35.79	.005	2	2	1.76	1	.01	2	.01	.01	.01	1	1
6H-87-07 93-94M	1	4	4	11	.2	8	1	66	.22	5	6	ND	1	324	1	2	8	2	35.82	.014	2	3	.47	2	.01	5	.01	.01	.01	2	1
6H-87-07 95-96M	1	15	3	12	.5	9	1	98	.30	6	6	ND	1	293	1	2	8	4	35.79	.015	2	3	.53	2	.01	2	.01	.01	.01	1	1
6H-87-07 97-98M	2	20	5	13	.3	14	1	104	.44	9	7	ND	1	253	1	2	5	6	35.77	.019	2	1	1.20	4	.01	2	.01	.01	.01	1	1
6H-87-07 99-100M	2	6	3	38	.5	5	1	58	.25	5	5	ND	1	292	1	2	6	2	35.78	.004	2	2	1.02	3	.01	2	.01	.01	.01	1	1
6H-87-07 100.4-101.4M	1	61	11	12	.3	41	35	48	2.56	20	5	ND	1	47	1	5	2	4	5.51	.151	2	1	.07	10	.01	2	.27	.01	.15	1	2
6H-87-07 103-104M	3	9	4	8	.3	7	1	65	.28	6	5	ND	1	218	1	4	7	4	35.45	.012	2	3	3.52	4	.01	10	.01	.01	.01	1	1
6H-87-07 105-106M	4	5	6	8	.2	6	1	57	.24	5	6	ND	1	183	1	3	7	3	35.26	.012	2	2	3.65	4	.01	2	.01	.01	.01	1	1
6H-87-07 107-108M	4	2	3	6	.1	3	1	218	.35	2	5	ND	1	134	1	2	10	4	27.85	.009	2	1	9.85	4	.01	2	.01	.01	.01	1	1
6H-87-07 109-110M	2	3	4	7	.3	3	1	80	.21	3	5	ND	1	170	1	2	10	4	32.03	.011	2	3	6.84	4	.01	3	.01	.01	.01	1	1
6H-87-07 111-112M	2	5	14	9	.3	8	1	95	.31	6	5	ND	1	215	1	5	7	4	33.15	.011	2	2	6.07	6	.01	4	.01	.01	.01	1	1
6H-87-07 113-114M	3	4	4	17	.3	7	1	146	.33	3	5	ND	1	217	1	3	7	5	32.11	.020	2	1	6.23	7	.01	3	.01	.01	.01	1	1
6H-87-07 115-116M	3	29	3	10	.1	19	9	224	.98	7	5	ND	1	154	1	3	2	4	14.96	.061	2	1	3.48	13	.01	2	.15	.01	.09	4	1
SIB C/AU-F	18	58	39	131	7.2	69	27	1019	3.90	39	22	7	36	48	18	17	20	55	.41	.089	36	59	.85	173	.08	37	1.80	.07	.13	13	485

GEOCHEMICAL ICF ANALYSIS

.500 GRAM SAMPLE IS DIGESTED WITH 3ML 3-1-2 HCL-HNO₃-H₂O AT 95 DEG.C FOR ONE HOUR AND IS DILUTED TO 10 ML WITH WATER.
THIS LEACH IS PARTIAL FOR MN FE CA P LA CR MG BA TI B W AND LIMITED FOR NA AND K. NO DETECTION LIMIT BY ICP IS 3 PPM.
- SAMPLE TYPE: Core AUC ANALYSIS BY AA FROM 10 GRAM SAMPLE.

DATE RECEIVED: SEPT 3 1987

DATE REPORT MAILED: *Sept 12/87*ASSAYER: *D. J. J. J.*

DEAN TOYE, CERTIFIED B.C. ASSAYER

STRYKER FREEPORT

File # 87-3886

SAMPLE#	NO	CU	PB	ZN	AG	NI	CO	MN	FE	AS	U	AU	TH	SR	CD	SB	BT	V	CR	P	LA	CR	MG	BA	TI	B	AL	NA	K	W	AUC
	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM
6H-87-06 83.2-84.2M	2	47	2	108	.1	36	19	824	6.00	9	5	ND	1	81	1	2	2	64	5.92	.075	3	41	2.94	17	.01	2	1.61	.05	.06	1	1
6H-87-06 118-119M	2	5	4	15	.2	10	1	78	.27	3	16	ND	1	437	1	2	3	4	31.70	.027	5	2	2.54	6	.01	8	.01	.01	.01	1	1
6H-87-06 122-123M	1	5	4	8	.4	5	1	66	.23	5	11	ND	1	350	1	2	3	5	30.84	.029	2	2	1.63	4	.01	2	.02	.01	.01	1	1
6H-87-06 124-125M	1	4	4	9	.2	6	1	61	.19	2	5	ND	1	262	1	2	3	5	26.53	.025	2	2	4.55	6	.01	15	.01	.01	.01	1	1
6H-87-06 125-126M	1	4	4	10	.4	5	1	95	.24	3	5	ND	1	276	1	3	5	5	27.32	.026	2	1	5.29	4	.01	2	.01	.01	.01	1	1
6H-87-06 127-128M	1	3	2	7	.4	5	1	73	.21	4	11	ND	1	494	1	2	2	3	32.52	.022	2	3	2.44	5	.01	4	.01	.01	.01	1	1
6H-87-06 129-130M	1	5	2	6	.5	7	1	75	.24	2	12	ND	1	461	1	3	3	5	31.08	.030	2	2	3.38	2	.01	5	.01	.01	.01	1	1
6H-87-06 131.3-131.6M	4	63	6	50	.1	22	18	243	4.48	19	5	ND	2	149	1	2	2	34	9.31	.058	3	4	1.89	25	.01	3	.49	.02	.08	1	1
6H-87-06 131.6-132.6M	1	3	4	7	.4	9	1	130	.28	2	6	ND	1	371	1	2	4	8	28.33	.032	2	3	5.58	5	.01	2	.02	.01	.01	1	1
6H-87-06 145-146M	3	4	2	30	.3	12	1	62	.29	4	5	ND	1	537	1	2	2	8	32.95	.031	3	3	2.37	4	.01	2	.05	.01	.02	1	1
6H-87-06 149.9-150.6M	4	55	9	155	.5	85	21	183	2.00	18	5	ND	2	149	1	2	2	26	13.87	.135	4	20	.72	49	.01	5	.72	.01	.18	1	1
6H-87-06 162-163M	1	2	2	8	.4	4	1	26	.19	4	6	ND	1	357	1	2	3	2	38.28	.012	2	4	.58	4	.01	2	.03	.01	.02	1	1
6H-87-07 145-146M	1	56	3	7	.5	8	1	52	.49	7	6	ND	1	338	1	2	3	4	38.53	.002	2	2	.79	4	.01	2	.02	.01	.02	1	1
STD C/AU-8	19	60	43	132	7.3	69	28	1052	4.04	43	16	7	39	51	18	17	18	58	.48	.041	28	60	.64	162	.08	34	1.86	.08	.14	13	510

GEOCHEMICAL ICP ANALYSIS

.500 GRAM SAMPLE IS DIGESTED WITH 3ML 3-1-2 HCL-HNO3-H2O AT 95 DEG.C FOR ONE HOUR AND IS DILUTED TO 10 ML WITH WATER.
THIS LEACH IS PARTIAL FOR NH FE CA P LA CR MG BA TI B W AND LIMITED FOR NA AND K. AU DETECTION LIMIT BY ICP IS 3 PPM.
- SAMPLE TYPE: P1-CORE P2-S ROCK AU ANALYSIS BY AA FROM 10 GRAM SAMPLE.

DATE RECEIVED: SEPT 11 1987

DATE REPORT MAILED:

Sept 22/87

ASSAYER:

D. J. J. J.

DEAN TOYE, CERTIFIED B.C. ASSAYER

STRYKER FREEPORT

File # 87-4065

Page 1

SAMPLE	NO	CU	PB	ZN	AG	NI	CO	MN	FE	AS	U	AU	TH	SR	CD	SB	BI	V	CA	P	LA	CR	MG	BA	TI	B	AL	NA	K	W	AUX
	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	1	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	1	1	PPM	PPM	1	PPM	1	PPM	1	1	1	PPM	PPM
GM 87 07 117.3-118.5	1	35	2	8	.1	23	15	55	1.35	14	5	ND	1	49	1	2	2	3	4.24	.084	2	3	.26	11	.01	2	.25	.02	.15	1	13
GM 87 07 119.2-120.2	2	10	3	17	.3	9	1	100	.26	10	5	ND	1	332	1	3	2	5	30.93	.016	2	1	2.40	4	.01	2	.01	.01	.01	1	4
GM 87 07 121-122	1	2	2	3	.3	3	1	73	.19	4	5	ND	1	308	1	3	2	5	30.87	.004	2	1	2.44	3	.01	2	.01	.01	.01	1	1
GM 87 07 123-124	2	5	2	3	.2	7	1	47	.23	5	5	ND	1	339	1	2	3	2	30.83	.017	2	1	.51	3	.01	2	.01	.01	.01	1	1
GM 87 07 125-126	1	4	2	4	.3	11	1	34	.16	2	5	ND	1	298	1	2	7	2	30.83	.009	2	3	.46	2	.01	2	.01	.02	.01	1	1
GM 87 07 127-128	2	6	3	5	.2	5	1	60	.24	5	5	ND	1	316	1	3	2	3	30.86	.004	2	1	1.81	2	.01	6	.01	.02	.01	1	2
GM 87 07 129-130	2	5	2	6	.2	7	1	170	.32	4	5	ND	1	241	1	2	2	2	30.86	.007	2	1	3.03	2	.01	2	.01	.01	.01	1	1
GM 87 07 137-138	1	3	2	5	.1	3	1	89	.22	4	5	ND	1	186	1	2	4	4	30.59	.010	2	2	5.43	3	.01	5	.01	.01	.01	1	118
GM 87 07 139-140	1	3	3	6	.1	3	1	136	.32	2	5	ND	1	184	1	2	5	4	30.17	.010	2	1	6.03	4	.01	3	.01	.01	.01	1	1
GM 87 07 141-142	1	4	2	8	.1	3	1	158	.28	3	5	ND	1	145	1	2	7	5	29.52	.018	2	2	6.90	2	.01	2	.01	.01	.01	1	1
GM 87 07 143-144	1	2	5	4	.2	3	1	133	.21	4	5	ND	1	180	1	2	5	4	30.30	.005	2	1	5.87	2	.01	2	.01	.01	.01	1	1
GM 87 07 147-148	1	2	2	2	.2	1	1	45	.16	2	5	ND	1	346	1	3	2	3	30.86	.002	2	2	1.96	4	.01	2	.02	.01	.01	1	1
GM 87 07 149-150	2	15	3	4	.2	3	1	61	.22	2	5	ND	1	313	1	3	2	5	30.85	.002	2	1	2.94	4	.01	2	.01	.01	.01	1	1
GM 87 07 151-152	1	2	2	5	.1	2	1	60	.19	2	5	ND	1	255	1	2	3	5	30.80	.002	2	1	4.77	4	.01	2	.01	.01	.01	1	1
GM 87 07 153-154	1	4	2	6	.2	3	1	152	.28	3	5	ND	1	275	1	2	4	5	30.61	.004	2	1	5.59	3	.01	4	.01	.01	.01	1	1
GM 87 07 155-156	1	55	9	74	.2	33	23	599	5.59	5	5	ND	1	83	1	8	2	63	7.08	.052	2	57	4.03	9	.01	2	2.48	.02	.04	1	1
GM 87 07 157-158	1	3	3	3	.3	3	1	102	.23	5	5	ND	1	342	1	2	2	3	30.92	.002	2	2	2.00	2	.01	2	.01	.01	.01	1	2
GM 87 07 159-160	1	3	2	2	.3	3	1	47	.19	3	5	ND	1	322	1	2	2	2	30.83	.002	2	1	1.71	2	.01	2	.02	.02	.01	1	10
GM 87 07 161-162	1	5	2	4	.2	2	1	60	.17	2	5	ND	1	201	1	2	2	4	30.75	.003	2	1	4.91	3	.01	6	.01	.01	.01	1	2
GM 87 07 163-164	1	1	3	3	.3	2	1	47	.18	2	5	ND	1	323	1	2	2	3	30.86	.008	2	2	2.21	3	.01	2	.01	.01	.01	1	1
GM 87 07 165-166	2	2	3	10	.2	6	1	67	.29	2	5	ND	1	324	1	3	2	8	30.86	.009	2	1	2.86	9	.01	5	.01	.02	.01	1	1
GM 87 07 167-168	1	1	2	7	.3	3	1	34	.18	3	5	ND	1	494	1	2	4	5	30.82	.004	2	1	.56	14	.01	2	.01	.02	.01	1	1
GM 87 07 169-170	1	3	2	6	.2	4	1	76	.23	4	5	ND	1	288	1	2	3	13	30.83	.007	2	1	4.63	6	.01	4	.02	.01	.01	1	1
GM 87 07 171-172	1	3	2	9	.3	3	1	48	.16	3	5	ND	1	304	1	3	2	6	30.94	.013	2	1	2.80	3	.01	7	.02	.01	.01	1	1
GM 87 07 173-174	2	3	3	5	.3	6	1	166	.28	2	5	ND	1	412	1	3	2	6	30.87	.013	4	2	2.07	4	.01	2	.04	.01	.01	1	2
GM 87 07 175-176	2	46	8	67	.3	13	17	822	5.18	3	5	ND	2	84	1	6	2	65	7.41	.074	4	34	2.63	18	.01	2	1.52	.04	.06	1	3
GM 87 07 177-178	2	5	2	11	.1	4	1	76	.22	4	5	ND	1	228	1	2	7	5	27.73	.015	2	1	7.41	4	.01	2	.02	.01	.01	1	1
GM 87 07 179-180	1	4	3	12	.1	6	1	90	.27	5	5	ND	1	234	1	2	3	3	30.11	.011	2	1	4.96	10	.01	2	.02	.01	.01	1	1
GM 87 07 181-182	1	5	2	8	.3	4	1	41	.17	6	5	ND	1	260	1	2	2	2	30.83	.008	2	1	3.78	8	.01	2	.01	.01	.01	1	2
GM 87 07 183-184	1	3	2	9	.2	3	1	145	.27	3	5	ND	1	263	1	2	8	6	28.86	.005	2	1	7.21	5	.01	2	.01	.01	.01	1	1
GM 87 07 185-186	1	2	3	7	.1	2	1	60	.16	2	5	ND	1	289	1	2	2	3	30.84	.010	2	1	4.21	5	.01	2	.01	.01	.01	1	1
GM 87 07 187-188	1	2	3	12	.3	4	1	82	.24	5	5	ND	1	255	1	2	4	4	30.56	.015	2	1	4.98	12	.01	2	.03	.01	.02	1	2
GM 87 07 189-190	1	3	2	18	.3	4	1	205	.37	4	5	ND	1	302	1	2	4	4	30.42	.020	2	1	5.63	7	.01	2	.02	.01	.01	1	2
GM 87 07 191-192	1	3	2	16	.2	3	1	65	.21	4	5	ND	1	317	1	2	3	4	30.68	.017	2	1	4.68	7	.01	5	.01	.01	.01	1	1
GM 87 07 193-194	1	4	2	11	.3	4	1	286	.49	4	5	ND	1	323	1	2	5	6	27.52	.011	2	1	6.48	8	.01	2	.02	.01	.01	1	2
GM 87 07 195-196	1	6	3	9	.3	2	1	119	.22	2	5	ND	1	345	1	2	5	5	29.48	.012	2	1	5.98	7	.01	2	.01	.01	.01	1	1
STD C/AU-R	18	57	41	132	7.2	67	26	1027	3.91	38	25	7	39	49	17	16	19	55	.47	.085	37	58	.86	175	.08	33	1.80	.08	.13	12	495

GEOCHEMICAL ICP ANALYSIS

.500 GRAM SAMPLE IS DIGESTED WITH 3ML 3-1-2 HCL-HNO₃-H₂O AT 95 DEG.C FOR ONE HOUR AND IS DILUTED TO 10 ML WITH WATER.
THIS LEACH IS PARTIAL FOR AM FE CA P LA CR MG BA TI B W AND LIMITED FOR NA AND K. AU DETECTION LIMIT BY ICP IS 3 PPM.
- SAMPLE TYPE: CORE/ROCK AU ANALYSIS BY AA FROM 10 GRAM SAMPLE.

DATE RECEIVED: SEPT 14 1987

DATE REPORT MAILED: *Sep 26/87*ASSAYER: *D. J. J.* DEAN TOYE, CERTIFIED B.C. ASSAYER

STRYKER FREEPORT RES.

File # 87-4184

SAMPLE#	NO	CU	PB	ZN	AG	NI	CO	MN	FE	AS	U	AU	TH	SR	CD	SB	BI	V	CA	P	LA	CR	MG	BA	TI	B	AL	NA	K	W	AU
	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM	PPM
6H87-06-84.2-84.6M	2	16	39	221	1.3	83	24	1024	9.50	89	6	ND	2	263	1	2	2	20	7.59	.067	6	1	2.62	9	.01	2	.11	.04	.03	1	201
6H87-07-131-132M	3	3	117	30	1.7	5	1	473	.60	10	7	ND	1	251	1	2	2	4	16.04	.007	5	1	3.62	4	.01	10	.01	.01	.01	3	1
6H87-07-133-134M	2	3	13	22	.5	6	1	288	.64	4	5	ND	1	147	1	2	2	7	12.63	.009	2	1	5.11	3	.01	2	.02	.01	.01	1	2
6H87-07-135-136M	1	2	62	31	.5	2	1	114	.21	2	8	ND	1	134	1	2	2	6	13.04	.008	2	1	5.11	4	.01	2	.01	.01	.01	3	1
6H87-07-196-196.9M	1	5	6	21	.5	6	1	129	.25	2	5	ND	1	448	1	2	2	7	16.11	.014	2	1	3.31	9	.01	10	.02	.01	.01	2	1
6H87-07-196.9-197.1M	3	36	33	27	.7	20	5	691	2.96	12	5	ND	1	249	1	2	2	61	6.60	.062	2	7	3.03	98	.01	13	.32	.07	.09	1	1
6H87-07-197.1-197.45M	1	7	7	30	.7	2	1	620	.97	2	5	ND	1	193	1	2	2	12	9.09	.008	11	1	.81	68	.01	13	.04	.03	.01	2	1
6H87-07-197.45-198.2M	2	127	20	42	.6	20	17	849	5.54	16	5	ND	1	83	1	2	2	27	4.50	.065	3	7	1.73	33	.01	2	.37	.04	.12	1	2
6H87-07-198.2-199M	4	39	8	47	.4	27	3	981	2.18	3	5	ND	1	74	1	3	2	18	4.91	.046	3	2	.77	70	.01	4	.24	.04	.09	3	1
6H87-07-199-201.5M	4	83	16	43	.6	22	17	686	4.31	8	5	ND	1	82	1	2	2	25	4.91	.087	3	4	1.38	39	.01	2	.45	.05	.12	1	1
STD C/MU-R	18	59	38	128	7.6	68	27	1034	3.85	38	18	7	39	50	18	17	20	56	.48	.085	38	62	.86	171	.08	36	1.82	.09	.13	13	510
6H87-07-201.5-202.0M	7	93	6	30	.4	29	14	869	4.47	4	5	ND	2	107	1	2	2	22	4.48	.084	4	1	1.39	50	.01	2	.41	.04	.13	1	1
6H87-07-202.0-203.5M	18	29	18	35	.5	84	5	948	1.65	6	5	ND	1	313	1	3	2	30	11.16	.056	6	5	.67	42	.01	10	.19	.03	.08	2	9
6H87-07-203.5-204.5M	23	57	4	19	.5	127	6	451	1.89	4	5	ND	4	254	1	2	2	28	6.35	.100	5	5	.48	49	.01	2	.25	.04	.11	2	6
6H87-07-204.5-205M	19	58	13	23	.3	117	9	595	2.68	5	5	ND	4	150	1	2	2	24	5.15	.107	5	11	1.15	55	.01	10	.22	.04	.08	1	1
6H87-07-205-205.35M	5	535	16	21	1.0	138	86	663	18.74	23	5	ND	3	57	1	2	5	12	3.62	.013	5	2	.63	13	.01	2	.08	.04	.04	2	19
6H87-07-205.35-206.2M	2	86	4	26	.4	24	15	808	4.37	2	5	ND	1	106	1	2	2	11	4.64	.036	2	3	2.23	40	.01	2	.31	.05	.11	1	2
6H87-07-207-208M	62	114	19	37	.5	363	12	506	3.45	5	5	ND	3	204	1	2	2	77	5.82	.029	3	3	.79	27	.01	4	.15	.03	.07	1	13
6H87-07-209-210M	32	55	5	33	.3	116	5	354	1.70	6	5	ND	4	143	1	2	2	25	4.85	.023	6	1	.86	28	.01	2	.18	.04	.08	1	1
6H87-07-211-212M	68	56	27	1432	.5	171	4	234	1.73	2	5	ND	1	175	15	2	2	135	4.13	.044	4	7	.49	30	.01	2	.17	.03	.08	1	18
6H87-07-213-214M	36	52	4	777	.4	109	5	378	1.65	2	5	ND	4	183	8	2	2	42	5.52	.023	7	4	1.05	26	.01	3	.18	.04	.06	1	7
6H87-07-215-216M	47	37	13	2396	.3	119	4	326	1.44	3	5	ND	1	444	24	2	2	66	7.57	.027	4	4	.36	20	.01	2	.11	.02	.04	1	46
6H87-07-217-218M	103	55	10	2941	.7	290	4	234	1.56	2	6	ND	3	160	30	2	2	158	4.18	.046	6	6	.52	32	.01	2	.18	.03	.09	1	45
6H87-07-218.7-219.7	99	52	15	3136	.5	255	5	202	1.67	3	7	ND	3	92	32	2	2	123	2.97	.035	6	9	.60	32	.01	11	.18	.04	.08	2	54
6H87-07-219.7-220.7M	4	83	10	185	.5	25	17	492	4.46	6	6	ND	2	97	2	3	2	13	4.04	.044	3	9	2.11	17	.01	2	.27	.07	.06	1	1
6H87-07-220.7-221.6M	1	196	7	57	.3	24	18	611	4.56	7	5	ND	1	103	1	4	2	10	4.30	.041	4	12	2.43	15	.01	2	.32	.07	.04	1	1
6H87-07-221.6-221.8M	15	195	6	13685	.6	89	23	695	5.51	16	5	ND	1	290	139	2	2	29	7.91	.011	2	6	.57	9	.01	5	.05	.03	.02	1	36
6H87-07-221.8-222M	43	33	17	1947	.4	108	8	366	2.34	4	5	ND	1	131	19	2	2	73	4.39	.022	2	5	.65	16	.01	8	.09	.03	.03	1	22
6H87-07-222-223M	106	73	8	2716	.5	357	7	240	1.96	2	6	ND	3	173	27	2	2	155	3.91	.048	7	6	.36	33	.01	2	.18	.03	.07	1	38
6H87-07-223-224M	59	76	8	693	.3	191	9	191	2.55	2	5	ND	6	63	7	2	2	45	2.13	.028	8	5	.46	32	.01	3	.20	.05	.08	1	17
6H87-07-225-226M	41	69	6	59	.4	169	9	259	2.65	2	7	ND	7	105	1	2	2	33	2.93	.031	9	5	.52	38	.01	3	.23	.05	.10	1	1
6H87-07-226-227M	40	57	7	19	.4	138	7	356	2.25	2	5	ND	5	144	1	2	2	28	4.00	.021	4	4	.54	37	.01	6	.21	.05	.08	1	1
6H87-07-227-228M	38	60	3	23	.4	137	8	439	2.72	5	5	ND	5	164	1	2	2	39	4.10	.038	6	9	.78	42	.01	2	.33	.07	.12	1	1
6H87-07-228-228.6M	1	37	6	79	.4	11	17	515	5.15	4	5	ND	2	96	1	2	2	27	3.77	.066	6	7	2.17	23	.01	3	.75	.10	.08	1	1
6H87-05 117.5M	4	559	25	122	1.3	13	22	1169	10.88	20	5	ND	1	37	1	2	2	108	2.52	.051	2	5	1.62	13	.10	3	2.57	.22	.49	1	1
6H87-02	4	2842	22	294	.7	20	9	1516	2.60	9	5	ND	1	310	2	2	2	42	7.46	.049	7	29	.61	23	.01	2	.49	.03	.02	1	1
6H87-03	211	41127	492	3149	66.3	12	11	210	22.29	22	7	ND	3	77	11	2	4	184	.08	.083	9	32	.97	27	.09	2	1.85	.08	.05	1	810