

WHITEHORSE COPPER MINES  
Whitehorse

EXPLORATION ASSAY DATA

Property North Star

Date 28/10/01  
Page No. 1 of 3

Sample No.	Hole No.	Footage		Length	Rec.	%Cu	%Moly	Au/Ag	%Fe	Remarks
		From	To							
9926	14515W2	1681.5	1688	6.5	6.5	.45	✓	.16		
27			1693	5	5	.17	✓	.06		
28			1698	5	5	.17	✓	.06		
29		1698	1703	5	5	1.37	✓	.15		6.85
30			1708	5	5	4.20	✓	.96		21.00
31		1708	1712.8	4.8	4.8	3.01	✓	.87		14.45
			dip 11.7'							LT 10°
32		1724.5	1729	4.5	4.5	1.84	✓	.69		8.28
33		1729	1735	6	6	1.05	✓	.52		6.30
34		1735	1740	5	5	.86	✓	.32		4.3
35		1740	1745	5	5	2.13	✓	.69		10.65
36		1745	1750	5	4.5	.17	✓	.09		
99 37		1750	1755	5	5	.06	✓	.08		
9938		1459	1466.8	7.8	7.5	.41	✓	.08		
- dyp c										
9939		1468	1472	5	5	.88	✓	.10		
40		1472	1477	5	5	1.70	✓	.70		
41		1477	1482.8	6.8	6.8	.76	✓	.13		
42		1492.4	1492.4	5	5	.13	✓	.05		
43		1587	1596.3	3.3	3.3	2.13	✓	.84		
		1590.3	1596.3	4.0	4.0	5/3	✓			
9944		1594.3	1600	5.7	5.7	2.68	✓	.55		
9947		1873.3	1877	3.7	3.7	1.14	✓	.41		
9948		1877	1882	5.0	4.7	.69	✓	.23		
9945		1777	1782	5	5	.01	✓	.06		
9946		1782	1787	5	5	.16	✓	.09		
9949		1446	1448	2	1.5	1.08	✓	.037		
9950		1452.3	1456	3.7	3.7	0.21	✓	.010		
9951		1609.8	1617	7.2	7.2	0.34	✓	.011		

WHITEHORSE COPPER MINES  
Whitehorse

EXPLORATION ASSAY DATA

Property NORTH STAR 15 W 2

Date \_\_\_\_\_  
Page No. 2 of 3

Sample No.	Hole No.	Footage		Length	Rec.	%Cu	%Moly	Au/Ag	%Fe	Remarks
		From	To							
9883	14515W2	984.1	987	2.9	2.9	1.57		.22		
		recovered for wedge								
9884		990	994	4	5	4.42		.81		
9885		1097	1099.5	2.5	2.5	1.79		.65		
9886		1106.5	1107.6	1.1	1.1	1.33		.40		
9887		1114	1115.2	1.2	1.2	.83		.27		
9888		1148	1152	4	4	.18		.31		
9889		1153.8	1159	5.2	5.2	.83		.59		
9890		1196.7	1202	5.3	4.8	.61		.14		
		1698	1712.8	14.8	14.8	2.86	42.798	.66		
		1724.5	1745	20.5	20.5	1.44	29.53	.55		
		1698	1745	47	47	1.53	71.83	.75		
		1467	1482.8	16.8	16.8	1.05	18.07	.29		
		1587	1600	13	13	1.71	22.3	.66		
		1873.3	1882	8.7	8.4	0.88	7.67	.31		

## EXPLORATION ASSAY DATA

Date \_\_\_\_\_  
Page No. 3 of 3

Sample No.	Hole No.	Footage		Length	Rec.	%Cu	%Moly	Au/Ag	%Fe	Remarks
		From	To							
9952	NS15W2	1882	1887.5	5.3	5.3	0.47		0.17		
9953		1887.5	1895	7.5	7.5	0.31		0.10		
9954		1895	1905	10	10	0.21		0.08		
9955		1923	1927	4	4	0.43		0.12		
9956		1927	1932	5	5	0.05		0.09		
9957		1969.2	1977	7.8	7.8	0.07				
9958		1977	1983	6	6	0.40				
9959		1983	1987.5	4.5	4.5	1.36				
9960		2131	2136	5	5	0.60				
9961		2159	2164	5	5	0.84				
9962		2164	2169	5	5	1.16				
9963		2169	2174	5	5	1.08				
9964		2174	2177.4	3.4	3.4	2.52				
9965		2201.8	2210	8.2	8.2	.14				
9966		2210	2215	5	5	3.32		0.61		
		2159	2177.4	18.4	18.4	1.30	23.97			