

EXPLORATION ASSAY DATA

Date Aug. 27th 81.
Page No. D.T. 102

Sample No.	Hole No.	Footage		Length	Rec.	%Cu	%Moly	Au/Ag ^{P.P.}	%Zn	Remarks
		From	To							
9855	NS 15	1369.5	1376.8	7.3	6.8	.08		250 103	.004	
56		1376.8	1382	5.2	5.2	3.09		170 70	.008	
57		1382	1387	5.0	5.0	3.32		200 117	.004	
58		1387	1393.8	6.8	6.4	5.42		200 131	.004	
59		1393.8	1398.8	5.0	5.0	5.14		270 97	.004	
60		1398.8	1403	4.2	4.2	.05		250 09	.0	
61		1403	1408	5.0	5.0	5.87		270 50	.004	
62		1408	1413	5.0	4.5	8.72		3290 63	.008	
63		1413	1418	5.0	5.0	7.57		680 56	.008	
64		1418	1424.8	6.8	6.8	5.33		960 108	.004	
65		1424.8	1429	4.2	4.2	.63		250 33	.004	
								C. 0.02000		
		1376.8 [✓]	1424.8 [✓]	48.0 [✓]	47.1	5.05	D.T.	678 82		
9851		363	367	4	4	0.314		0.17		
9852		392.8	3944	1.6	1.6	0.68		0.26		
9853		795.2	802	6.8	6.8	0.47		0.29		
9854		802	811	9	9	0.22		0.06		

EXPLORATION ASSAY DATA

Date _____
Page No. 2 of 2

Sample No.	Hole No.	Footage		Length	Rec.	%Cu	%Moly	Au/Ag	%Fe	Remarks
		From	To							
9866	N515	968.4	977.3	8.9	5.3	.15		.05		
68		1018.4	1019.1	0.7	0.7	.96		.17		
9868		1031	1036	4	4.5	.05		.02		
9869		1036	1040	4	4	.07		.05		
		1429								
9870		1429	1434.8	5.8	5.8	.02		.02		
9871		1434.8	1438.7	3.9	3.9	.48		.17		
9872		1632	1637.4	5.4	5.4	1.04		.08		
9873		1637.4	1642.4	5	5	0.92		.20		
9874		1684	1691	7	7	0.35		.05		
		1632	1642.4	10.4	10.4	0.98		.14		