

2008 PLATA DENSITY

DDH-PL-08-12	DMEsh	65.21	65.31	2.609	2.624	
DDH-PL-08-12	DMEch	102.18	102.28	2.973	2.989	
DDH-PL-08-13	PCHsh	71.65	71.75	2.815	2.831	
DDH-PL-08-13	PCHsh	89.85	89.95	2.839	2.861	
DDH-PL-08-13	DMEsh	103.18	103.28	2.675	2.702	
DDH-PL-08-14	PCHI	22.08	22.18	2.687	2.693	
DDH-PL-08-14	PCHsh	49.69	49.79	2.872	2.883	
DDH-PL-08-14	DMEsh	73.95	74.05	2.680	2.694	
DDH-PL-08-15	PCHsh	61.90	62.00	2.752	2.790	
DDH-PL-08-15	DMEsh	98.97	99.07	2.865	2.865	
DDH-PL-08-15	VEIN 70% S	90.29	90.39			2.369
DDH-PL-08-15	VEIN 80% S	90.37	90.47			3.694
DDH-PL-08-16	VEIN 90%+ Galena	12.85	12.95			6.379
DDH-PL-08-16	DMEsh	17.37	17.47		2.765	
DDH-PL-08-17	PCHQ	7.54	7.64	2.738	2.749	
DDH-PL-08-17	DMEsh	21.56	21.66	2.725	2.745	
DDH-PL-08-17	VEIN 70% S	16.34	16.44			3.988
DDH-PL-08-18	PCHQ	14.54	14.64	2.584	2.604	
DDH-PL-08-18	DMEsh	29.94	30.04	2.770	2.796	
DDH-PL-08-18	VEIN Quartz, <5% S	26.03	26.13			2.645
DDH-PL-08-19	VEIN 70% S	27.08	27.18			4.156
DDH-PL-08-19	VEIN 90% S	27.42	27.52			4.854
DDH-PL-08-20	VEIN 50%	96.92	97.02			4.200
DDH-PL-08-20	VEIN 70% S	99.57	99.67			3.782
DDH-PL-08-20	PCHsh	57.50	57.60	2.858	2.879	
DDH-PL-08-20	DMEsh	106.55	106.65	3.103	3.112	
DDH-PL-08-21	PCHsh	27.24	27.34	2.835	2.852	
DDH-PL-08-21	DMEsh	62.28	62.38	2.843	2.858	
DDH-PL-08-21	VEIN 25% S	33.87	33.97			3.072
DDH-PL-08-22	PCHQ	15.36	15.46	2.681	2.685	
DDH-PL-08-22	DMEsh	26.52	26.62	2.808	2.821	
DDH-PL-08-22	VEIN 80% S	20.16	20.26			4.854
DDH-PL-08-23	PCHQ	14.74	14.84	2.650	2.658	
DDH-PL-08-23	DMEsh	24.11	24.21	2.828	2.854	
DDH-PL-08-24	PCHQ	19.15	19.25	2.718	2.726	
DDH-PL-08-25	PCHQ	29.83	29.93	2.653	2.657	
DDH-PL-08-25	DMEsh	69.41	69.51	2.789	2.813	
DDH-PL-08-26	PCHsh	60.37	60.47	2.828	2.851	