



ALS Chemex

EXCELLENCE IN ANALYTICAL CHEMISTRY

ALS Canada Ltd.

212 Brooksbank Avenue

North Vancouver BC V7J 2C1

Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

To: STRATEGIC METALS LTD.
C/O ARCHER, CATHRO & ASSOCIATES (1981) LIMITED
1016-510 W HASTINGS ST
VANCOUVER BC V6B 1L8

Page: 1
Finalized Date: 30-SEP-2007
Account: MTT

CERTIFICATE VA07098284

Project: NIMO RICH

P.O. No.: RI07-06

This report is for 28 Drill Core samples submitted to our lab in Vancouver, BC, Canada on 15-AUG-2007.

The following have access to data associated with this certificate:

AL ARCHER
VANCOUVER OFFICE

DOUG EATON
BILL WENGZYNOWSKI

JOAN MARIACHER

SAMPLE PREPARATION

ALS CODE	DESCRIPTION
WEI-21	Received Sample Weight
LOG-22	Sample login - Rcd w/o BarCode
CRU-31	Fine crushing - 70% <2mm
SPL-21	Split sample - riffle splitter
PUL-36	Pulverize 1.5 kg to 85% <75 um
CRU-QC	Crushing QC Test
BAG-01	Bulk Master for Storage

ANALYTICAL PROCEDURES

ALS CODE	DESCRIPTION	INSTRUMENT
Hg-CV41	Trace Hg - cold vapor/AAS	FIMS
ME-MS61	48 element four acid ICP-MS	

To: STRATEGIC METALS LTD.
C/O ARCHER, CATHRO & ASSOCIATES (1981) LIMITED
1016-510 W HASTINGS ST
VANCOUVER BC V6B 1L8

This is the Final Report and supersedes any preliminary report with this certificate number. Results apply to samples as submitted. All changes of this report have been checked and approved for release.

Signature:

Lawrence Ng, Laboratory Manager - Vancouver



ALS Chemex

EXCELLENCE IN ANALYTICAL CHEMISTRY

ALS Canada Ltd.

212 Brooksbank Avenue

North Vancouver BC V7J 2C1

Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

TO: STRATEGIC METALS LTD.

C/O ARCHER, CATHRO & ASSOCIATES (1981)

LIMITED

1016-510 W HASTINGS ST

VANCOUVER BC V6B 1L8

Project: NIMO RICH

Page: 2 - A

Total # pages: 2 (A - D)

Finalized Date: 30-SEP-2007

Account: MTT

CERTIFICATE OF ANALYSIS VA07098284

Method	WEI-21	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61
Analyte	Recvd Wt.	Ag	Al	As	Ba	Be	Bi	Ca	Cd	Ce	Co	Cr	Cs	Cu	Fe	
Units	kg	ppm	%	ppm	ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	%	
LOR	0.02	0.01	0.01	0.2	10	0.05	0.01	0.01	0.02	0.01	0.1	1	0.05	0.2	0.01	
C488171	2.36	0.4	2.11	14.5	510	1.15	0.07	0.08	3.51	15.2	5.7	43	2.37	42.3	1.27	
C488172	2.60	0.34	2.1	12.3	370	1.18	0.03	0.1	3.46	17.75	4.9	40	2.5	39	1.31	
C488173	1.76	0.65	2.15	16	420	1.12	0.03	0.66	12.5	15.65	5.7	47	2.46	63.4	1.72	
C488174	1.58	0.51	1.76	14.5	540	1.11	0.08	0.08	9.53	13.6	4.3	51	2.19	44.1	1.36	
C488175	0.90	0.31	1.42	12.7	1010	0.95	0.08	0.72	4.06	14.1	4.3	38	1.71	35.3	1.51	
C488176	0.82	0.37	1.42	15.2	670	1.02	0.08	0.05	4.99	11.85	3.7	45	1.69	38.4	1.56	
C488177	0.86	0.43	1.34	13.8	940	1.12	0.07	0.05	12	11.35	3.7	51	1.69	53.9	1.41	
C488178	1.02	0.05	0.06	<5	20	0.1	0.02	19.85	0.1	1.29	0.9	1	0.17	1.4	0.42	
C488179	0.46	0.8	2.35	27.1	280	1.55	0.12	0.92	10.5	18.05	6.5	80	2.49	84.5	2.5	
C488181	0.66	0.09	0.06	<5	30	0.07	0.02	19.25	0.11	1.1	0.9	2	0.13	1.6	0.43	
C488182	0.42	0.44	1.83	18.4	500	1.26	0.11	0.23	3.3	18.9	4.5	45	2.18	42.6	1.54	
C488183	0.76	0.33	1.78	15.1	580	1.31	0.08	0.12	2.14	12.65	4.7	43	2.26	35.2	1.82	
C488184	0.86	0.27	1.83	13	740	1.45	0.09	0.2	2.13	16.95	4.6	39	2.47	31.7	1.34	
C488185	0.78	0.23	1.79	12.4	370	1.35	0.08	0.31	1.71	14.85	7.1	39	2.22	33.2	2.12	
C488186	1.54	0.19	1.68	11.3	480	1.18	0.07	0.07	1.52	14.7	4.1	39	1.92	29.8	1.42	
C488187	1.76	0.15	1.42	12.1	450	0.95	0.08	0.08	1.22	11.35	4.8	45	1.5	38.3	1.66	
C488188	0.80	0.27	1.16	10.6	770	0.74	0.06	0.05	1.21	9.64	3.7	36	1.14	28	1.53	
C488189	0.82	0.18	1.65	18.6	440	1.17	0.08	0.05	1.02	19	5	42	1.82	37.6	1.73	
C488190	0.80	0.17	1.51	18.8	330	0.94	0.07	0.04	1.84	10.45	5.1	37	1.54	33.8	1.81	
C488191	0.48	0.25	1.7	24.1	360	0.89	0.08	0.18	1.92	9.61	7.2	38	1.74	40	2.36	
C488193	0.14	0.23	0.09	<5	60	0.08	0.02	19.45	0.08	1.2	1	3	0.13	4.3	0.48	
C488194	0.44	0.38	6.46	71.6	200	2.96	0.22	0.23	3.13	30.4	14.6	90	9.14	52.4	3.69	
C488195	0.96	0.2	3.68	36	130	1.55	0.17	16.8	1.73	22.4	8.4	32	5.19	26.2	1.84	
C488196	0.76	0.26	3.85	24	310	1.44	0.11	20.5	2.88	42.2	7.8	36	4.61	32.2	1.84	
C488197	1.80	0.34	5.3	34.3	160	1.73	0.16	1.85	4.83	38.5	10.6	58	6.4	39.9	2.76	
C488198	1.82	0.26	4.11	18.3	280	1.32	0.13	5.75	3.94	39.4	8.2	50	4.66	26	2.04	
C488199	2.08	0.3	5.72	23.1	120	1.87	0.17	2.38	3.73	42.5	10.9	55	6.8	33.6	2.6	
C488200	2.66	0.29	4.79	21.7	130	1.68	0.14	1.84	3.34	33.7	9.5	51	5.94	32.9	2.38	

Comments: Interference: Ca>10% on ICP-MS As,ICP-AES results shown. REE's may not be totally soluble in MS61 method.



ALS Chemex

EXCELLENCE IN ANALYTICAL CHEMISTRY

ALS Canada Ltd.

212 Brooksbank Avenue
North Vancouver BC V7J 2C1

Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

To: STRATEGIC METALS LTD.
C/O ARCHER, CATHRO & ASSOCIATES (1981)
LIMITED
1016-510 W HASTINGS ST
VANCOUVER BC V6B 1L8

Project: NIMO RICH

Page: 2 - B
Total # pages: 2 (A - D)
Finalized Date: 30-SEP-2007
Account: MTT

CERTIFICATE OF ANALYSIS VA07098284

Sample Description	Method	ME-MS61	ME-MS61	ME-MS61	Hg-CV41	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61
	Analyte	Ga	Ge	Hf	Hg	In	K	La	Li	Mg	Mn	Mo	Na	Nb	Ni
	Units LOR	ppm	ppm	ppm	ppm	ppm	%	ppm	ppm	%	ppm	ppm	%	ppm	ppm
		0.05	0.05	0.1	0.01	0.005	0.01	0.5	0.2	0.01	5	0.05	0.01	0.1	0.2
C488171		5.57	0.1	0.8	0.09	0.016	0.68	9.9	6.9	0.13	62	41.5	0.05	3.8	138.5
C488172		5.85	0.11	0.9	0.09	0.015	0.68	12.7	6	0.14	61	48.6	0.04	3.7	127.5
C488173		6.17	0.15	0.8	0.14	0.023	0.67	10.1	5.9	0.38	110	37.2	0.06	3.7	127.5
C488174		5.19	0.13	0.8	0.11	0.018	0.59	9.3	6.2	0.12	61	41.5	0.03	3.2	125.5
C488175		4	0.14	0.7	0.08	0.017	0.45	9.8	5.6	0.38	125	44.8	0.03	2.8	121.5
C488176		3.87	0.12	0.7	0.09	0.016	0.45	8.6	6.4	0.09	69	52	0.03	2.9	149.5
C488177		4.15	0.14	0.7	0.10	0.021	0.42	7.1	5.5	0.09	67	44.7	0.03	2.6	145
C488178		0.29	0.19	<0.1	<0.01	0.008	0.03	0.7	1	12.8	191	0.51	<0.01	0.3	8.7
C488179		6.67	0.2	1.2	0.14	0.024	0.75	12.8	7.6	0.58	106	46	0.04	4.7	207
C488181		0.32	0.23	<0.1	<0.01	0.006	0.02	0.6	0.9	12.4	189	0.74	0.01	0.2	7.6
C488182		4.92	0.17	0.9	0.12	0.015	0.6	15	5.3	0.17	68	41.6	0.03	3.4	169.5
C488183		4.7	0.16	0.9	0.08	0.016	0.58	7.9	5.9	0.15	91	45	0.03	3.3	132
C488184		4.93	0.14	0.7	0.08	0.016	0.6	11.9	5.8	0.19	72	40.7	0.03	3.2	130
C488185		4.58	0.14	0.8	0.07	0.016	0.57	8.9	6.5	0.24	149	47.1	0.04	3.4	189
C488186		3.98	0.12	0.8	0.06	0.015	0.53	9.4	7.5	0.1	64	40.8	0.03	3.1	146
C488187		3.73	0.11	0.7	0.06	0.012	0.43	6.8	6.3	0.11	92	46.2	0.04	2.9	144.5
C488188		2.71	0.11	0.5	0.06	0.01	0.33	6.1	8.7	0.07	79	39.3	0.03	2.2	119.5
C488189		4.27	0.15	0.8	0.12	0.013	0.47	11.6	6.1	0.12	76	52.4	0.03	3.3	148.5
C488190		3.84	0.14	0.7	0.12	0.012	0.42	5.4	7.8	0.09	83	47.3	0.03	2.8	173.5
C488191		6.36	0.19	0.8	0.10	0.018	0.45	4.8	5.4	0.16	148	40.7	0.03	3.1	212
C488193		0.32	0.08	<0.1	<0.01	0.011	0.03	0.8	0.7	12.6	222	0.93	0.01	0.2	3.3
C488194		23.8	0.46	2.5	0.15	0.062	2.13	8.6	14.4	0.51	121	66.5	0.12	10.7	459
C488195		11.4	0.2	1.4	0.08	0.042	1.15	10.2	6.5	0.44	158	31.4	0.09	5.7	214
C488196		10.6	0.19	1.5	0.12	0.039	1.19	26.6	5.4	0.49	191	32.4	0.08	6	117
C488197		13.95	0.18	2.1	0.14	0.047	1.6	22.8	7.5	0.72	182	36.8	0.09	8.3	139.5
C488198		10.6	0.15	1.7	0.10	0.037	1.24	22.4	5.5	0.42	128	26.1	0.13	6.4	93.5
C488199		14.85	0.14	2.3	0.13	0.044	1.65	23.5	6.5	0.46	112	30.3	0.15	8.7	111.5
C488200		12.3	0.14	1.8	0.12	0.041	1.41	19.2	5.6	0.42	97	35.2	0.11	7	132.5

Comments: Interference: Ca>10% on ICP-MS As,ICP-AES results shown. REE's may not be totally soluble in MS61 method.



ALS Chemex

EXCELLENCE IN ANALYTICAL CHEMISTRY

ALS Canada Ltd.

212 Brooksbank Avenue

North Vancouver BC V7J 2C1

Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

To: STRATEGIC METALS LTD.

C/O ARCHER, CATHRO & ASSOCIATES (1981)

LIMITED

1016-510 W HASTINGS ST

VANCOUVER BC V6B 1L8

Project: NIMO RICH

Page: 2 - C

Total # Pages: 2 (A - D)

Finalized Date: 30-SEP-2007

Account: MTT

CERTIFICATE OF ANALYSIS VA07098284

Sample Description	Method Analyte Units LOR	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61
		Pb	Rb	Re	S	Sb	Sc	Se	Sn	Sr	Ta	Te	Th	Ti	Tl
		ppm	ppm	ppm	%	ppm	ppm	ppm	ppm	ppm	ppm	ppm	ppm	%	ppm
		0.5	0.1	0.002	0.01	0.05	0.1	1	0.2	0.2	0.05	0.05	0.2	0.005	0.02
C488171		6.4	38.8	0.031	1.03	12.1	4.9	11	0.8	29.7	0.21	0.09	2.5	0.096	2.95
C488172		5.6	39.2	0.042	1.03	11.95	4.8	11	0.8	41.4	0.21	0.1	2.4	0.094	2.83
C488173		6.7	39.2	0.047	1.37	29.3	4.9	23	0.9	79.2	0.21	0.14	2.3	0.098	2.96
C488174		5.4	36.6	0.056	0.94	17.2	3.7	15	0.8	30.9	0.18	0.14	2.1	0.081	2.53
C488175		4.7	27.1	0.052	0.82	12.6	3.7	12	0.6	95.7	0.16	0.12	1.7	0.068	2.34
C488176		4.9	27.1	0.066	0.91	13.1	3.2	14	0.8	54.1	0.17	0.15	1.8	0.067	3.27
C488177		4.6	26	0.057	0.8	15.95	3.5	15	0.6	40.5	0.15	0.13	1.7	0.063	3.53
C488178		1.6	1.1	0.015	0.02	0.13	0.3	2	<0.2	49.9	<0.05	<0.05	<0.2	<0.005	0.02
C488179		7.6	43.6	0.058	1.78	18.25	5.5	26	1	39.2	0.26	0.28	2.4	0.122	6.9
C488181		1.5	1.2	0.008	0.02	0.15	0.4	1	0.2	46.6	<0.05	<0.05	<0.2	<0.005	0.04
C488182		6.9	35.7	0.048	1.29	11.45	4.4	19	0.6	50.9	0.2	0.22	2.3	0.094	3.53
C488183		5.4	36.3	0.05	1.05	8.57	4.1	15	0.7	30.6	0.19	0.13	2.1	0.079	2.86
C488184		5.7	38.2	0.042	0.99	6.34	4	11	0.7	45.8	0.19	0.11	2.2	0.084	2.46
C488185		5.2	34.3	0.048	0.96	5.76	4.5	12	0.8	50.5	0.18	0.11	2	0.079	2.6
C488186		4.9	31	0.053	0.9	4.3	3.7	10	0.9	45.2	0.18	0.12	2	0.073	2.33
C488187		4.8	25.7	0.041	0.85	3.27	3.5	10	2.7	47.2	0.16	0.1	1.7	0.064	2
C488188		3.9	20.2	0.033	0.73	2.41	2.7	10	0.8	60.9	0.12	0.07	1.3	0.048	1.91
C488189		5.6	30.8	0.037	1.13	3.88	4.1	15	0.7	65.8	0.2	0.09	1.9	0.076	3.24
C488190		5.2	26.4	0.042	1.05	4.23	3.7	16	0.8	60.6	0.17	0.09	1.8	0.068	3.44
C488191		4.9	29.9	0.045	1.05	5.5	4.3	29	0.8	135.5	0.19	0.22	1.9	0.075	4.06
C488193		1.4	1.3	<0.002	0.03	0.16	0.6	2	0.2	44.2	<0.05	0.05	<0.2	<0.005	0.05
C488194		11.8	146.5	0.129	3.48	14.95	13.2	73	2.4	147	0.69	0.27	4.9	0.311	10.1
C488195		6.1	83.9	0.056	2.01	7.81	8.1	29	1.2	294	0.35	0.09	3.2	0.173	4.41
C488196		8.8	81.6	0.037	2.1	7.59	8.9	22	1.3	230	0.37	0.07	4.5	0.18	4.24
C488197		11.8	111.5	0.036	2.65	8.76	10.6	22	1.9	109.5	0.54	0.09	6.5	0.272	5.5
C488198		8.9	83.1	0.022	2.12	5.91	8.2	10	1.5	169	0.4	0.06	5.1	0.207	3.71
C488199		11.9	116	0.022	2.66	6.72	11.1	11	1.9	106.5	0.57	0.08	7	0.292	4.5
C488200		10.4	97.6	0.031	2.4	5.18	9.8	10	1.7	92.7	0.45	0.08	5.6	0.232	4.8

Comments: Interference: Ca>10% on ICP-MS As, ICP-AES results shown. REE's may not be totally soluble in MS61 method.



ALS Chemex

EXCELLENCE IN ANALYTICAL CHEMISTRY

ALS Canada Ltd.

212 Brooksbank Avenue

North Vancouver BC V7J 2C1

Phone: 604 984 0221 Fax: 604 984 0218 www.alschemex.com

To: STRATEGIC METALS LTD.

C/O ARCHER, CATHRO & ASSOCIATES (1981)

LIMITED

1016-510 W HASTINGS ST

VANCOUVER BC V6B 1L8

Project: NIMO RICH

Page: 2 - D

Total Pages: 2 (A - D)

Finalized Date: 30-SEP-2007

Account: MTT

CERTIFICATE OF ANALYSIS VA07098284

Sample Description	Method Analyte Units LOR	ME-MS61	ME-MS61	ME-MS61	ME-MS61	ME-MS61
		V	W	Y	Zn	Zr
		ppm 1	ppm 0.1	ppm 0.1	ppm 2	ppm 0.5
C488171		670	0.7	12.7	475	31.6
C488172		640	0.6	12.1	380	32.3
C488173		1045	1	22.6	1050	31.5
C488174		909	0.4	13.3	839	32.2
C488175		578	0.4	25.2	484	29.1
C488176		607	0.4	11.6	496	30.4
C488177		728	0.4	17.7	949	31.6
C488178		5	0.1	1	19	<0.5
C488179		876	0.6	16.3	794	50.7
C488181		5	0.1	0.9	17	0.6
C488182		526	0.6	16.3	324	35.4
C488183		486	0.4	20.5	245	35.8
C488184		493	0.5	16.8	285	31.7
C488185		425	0.5	35.1	446	34.7
C488186		355	0.4	13.3	203	31.4
C488187		287	0.4	15.2	213	29.5
C488188		141	1.7	8	88	24
C488189		194	0.4	10.7	128	33.3
C488190		383	0.5	14	311	30.2
C488191		529	0.4	17.8	677	38.7
C488193		7	0.1	1.1	18	0.7
C488194		944	1.2	24.4	573	93.6
C488195		538	0.6	36.2	277	47.6
C488196		607	0.7	60.7	271	50.2
C488197		829	0.9	13.6	406	69.8
C488198		567	0.7	22.1	325	55.9
C488199		705	1	20.4	322	70.6
C488200		686	0.8	15.2	285	59.8

Comments: Interference: Ca>10% on ICP-MS As,ICP-AES results shown. REE's may not be totally soluble in MS61 method.