

000465

File= HEADCOMP.WR1  
Bern. disk#7 CURRENT  
07-Aug-90CURRABH RESOURCES INC.  
GEOLOGY DEPARTMENT SUMMARY REPORT  
REPORTED HEADGRADE COMPARISON FROM VARIOUS SOURCES

Month	GEOLOGY				O.S.A.				MILL FINAL				24 HOUR COMPOSITE				MILL FINAL	FINAL TAILS
	Tonnage and Head Grade to CRUSHER Reported by Geology Department Each Day, Using Blasthole Data for grades and Truck Count for tonnage				Tonnage and Head Grade Reported by Mill Shift Reports Each Day, Using Average O.S.A. Reading, and Rod Mill Feed Total, by Weighometer.				Tonnage and Head Grade Reported by Mill on the Month to Date Production Summary.				Head Grade Reported by Assay Lab, from Composite Sample Taken at the Shark's fin Sampler. (mill final tonnage)				vs 24 HOUR COMPOSITE	from 24 hour composite
JULY 90	Tonnes	Pb%	Zn%	Pb+Zn	Tonnes	Pb%	Zn%	Pb+Zn	DMT	Pb%	Zn%	Pb+Zn	DMT	Pb%	Zn%	Pb+Zn	Pb+Zn	Pb+Zn
1	14,010	2.71	3.91	6.62	14,193	2.65	4.64	7.29	13,909	2.24	3.80	6.04	13,909	2.24	3.80	6.04	0.00	0.79
2	14,010	2.71	3.91	6.62	14,934	2.46	4.29	6.75	14,650	2.35	4.00	6.35	14,650	2.35	4.00	6.35	0.00	1.15
3	13,690	3.12	5.14	8.26	14,750	2.51	4.63	7.14	14,558	2.75	4.87	7.62	14,558	2.75	4.87	7.62	0.00	1.13
4	13,035	2.81	4.52	7.33	14,829	2.72	4.84	7.56	14,681	2.65	4.67	7.32	14,681	2.65	4.67	7.32	0.00	1.30
5	7,435	3.01	5.27	8.28	13,365	2.77	5.20	7.97	13,151	3.12	5.43	8.55	13,151	3.12	5.43	8.55	0.00	1.35
6	9,927	3.54	5.62	9.16	14,147	2.34	5.23	7.57	13,921	2.86	5.17	8.03	13,921	2.86	5.17	8.03	0.00	1.35
7	9,927	3.54	5.62	9.16	10,939	2.71	4.55	7.26	10,720	3.02	5.11	8.13	10,720	3.02	5.11	8.13	0.00	1.35
8	9,927	3.54	5.62	9.16	13,800	3.04	5.26	8.30	13,648	3.03	5.04	8.07	13,648	3.03	5.04	8.07	0.00	1.41
9	15,165	3.35	5.49	8.84	14,718	3.20	5.74	8.94	14,571	3.45	5.73	9.18	14,571	3.45	5.73	9.18	0.00	1.50
10	19,335	3.52	5.91	9.43	14,030	2.80	4.89	7.68	13,806	3.28	5.66	8.94	13,806	3.28	5.66	8.94	0.00	2.09
11	20,849	3.34	5.45	8.79	15,142	2.82	4.83	7.65	14,885	3.10	5.35	8.45	14,885	3.10	5.35	8.45	0.00	2.81
12	15,260	3.19	4.85	8.04	13,894	2.81	4.82	7.63	13,658	3.30	5.13	8.43	13,658	4.33	5.13	9.46	-1.03	1.75
13	13,983	3.25	5.22	8.47	14,337	2.76	4.56	7.32	14,151	2.81	4.52	7.33	14,151	2.81	4.52	7.33	0.00	1.50
14	13,983	3.25	5.22	8.47	14,862	2.61	4.38	6.99	14,594	2.92	4.39	7.31	14,594	2.92	4.39	7.31	0.00	1.50
15	13,983	3.25	5.22	8.47	14,636	2.82	5.16	7.98	14,358	2.82	5.16	7.98	14,358	2.82	5.16	7.98	0.00	1.44
16	8,340	3.13	5.09	8.22	13,192	3.05	5.38	8.43	13,034	3.34	5.33	8.67	13,034	4.34	5.33	9.67	-1.00	1.53
17	14,020	3.14	5.09	8.23	12,674	3.04	5.35	8.39	12,459	3.44	5.58	9.02	12,459	3.44	5.58	9.02	0.00	1.31
18	8,540	3.13	5.09	8.22	11,695	3.09	5.34	8.43	11,590	3.34	5.43	8.77	11,590	3.34	5.43	8.77	0.00	1.25
19	8,820	3.13	4.94	8.07	6,147	2.95	5.74	8.69	6,092	3.21	5.34	8.55	6,092	3.21	5.34	8.55	0.00	2.77
20	11,670	3.15	5.90	9.05	13,883	2.52	4.93	7.45	13,772	2.43	4.49	6.92	13,772	2.43	4.49	6.92	0.00	1.56
21	11,670	3.15	5.90	9.05	14,942	2.30	4.91	7.21	14,643	2.97	4.67	7.64	14,643	2.97	4.67	7.64	0.00	1.08
22	11,670	3.15	5.90	9.05	15,736	2.72	4.90	7.62	15,563	2.91	4.80	7.71	15,563	2.91	4.80	7.71	0.00	1.71
23	10,210	3.61	5.40	9.01	14,641	2.95	5.04	7.99	14,465	3.64	5.07	8.71	14,465	3.64	5.07	8.71	0.00	1.37
24	13,195	3.79	5.85	9.64	14,447	2.98	5.24	8.22	14,259	3.15	4.97	8.12	14,259	3.15	4.97	8.12	0.00	1.60
25	10,620	3.30	5.33	8.63	14,269	2.97	5.17	8.14	14,268	2.97	4.91	7.88	14,268	2.97	4.91	7.88	0.00	2.08
26	14,400	3.73	6.00	9.73	14,925	2.87	5.27	8.14	14,821	2.91	4.90	7.81	14,821	2.91	4.90	7.81	0.00	1.38
27	13,000	3.39	5.59	8.98	14,508	2.76	5.50	8.26	14,305	3.07	5.59	8.66	14,305	3.07	5.59	8.66	0.00	2.35
28	13,000	3.39	5.59	8.98	13,678	3.02	5.82	8.84	13,528	3.02	5.76	8.78	13,528	4.54	5.76	10.30	-1.52	1.57
29	13,000	3.39	5.59	8.98	14,443	2.84	4.82	7.66	14,270	3.31	4.67	7.98	14,270	3.31	4.67	7.98	0.00	1.49
30	13,840	3.39	5.72	9.11	13,772	2.80	5.03	7.83	13,510	3.04	5.11	8.15	13,510	3.04	5.11	8.15	0.00	1.82
31	17,370	3.39	5.72	9.11	14,506	2.84	5.08	7.92	14,187	3.07	4.99	8.06	14,187	3.07	4.99	8.06	0.00	1.81

NTD:	397,904	3.28	5.35	8.63	430,134	2.79	5.03	7.82	424,025	3.01	5.00	8.01	424,025	3.12	5.00	8.12	-0.114	1.583
		Pb+Zn=	8.63 %			Pb+Zn=	7.82 %			Pb+Zn=	8.01 %			Pb+Zn=	8.12		avg. daily adjustment by mill	avg. daily tails

Variance Percentage:	tonnes	%Pb	%Zn	Pb+Zn	Truck count factor:	1.080999
Geology vs O.S.A.	-8.10%	14.92%	5.94%	9.35%	Moisture content:	1.420 %
Geology vs Mill Final	-6.56%	8.29%	6.47%	7.16%		
Geology vs 24 hour Composite	-4.56%	4.87%	6.47%	5.86%	* Sample not available	
Mill Final vs 24 Hour Comp.	n/a	-3.74%	0.00%	-1.40%		