File= HEADCOMP.WR1
Bern. disk#8 \CURRENT
01-Oct-90

CURRAGH RESOURCES INC.
GEOLOGY DEPARTMENT SUMMARY REPORT
REPORTED HEADGRADE COMPARISON FROM VARIOUS SOURCES

000466

Month	GEOLOGY				D.S.A.				MILL FINAL				24 HOUR COMPOSITE				MILL FINAL vs 24 HOUR COMPOSITE	FINAL TAILS from 24 hour composite
	Tonnage and Head Grade to CRUSHER Reported by Geology Department Each Day, Using Blasthole Data for grades and Truck Count for tonnage				Tonnage and Head Grade Reported by Mill Shift Reports Each Day, Using Average D.S.A Reading, and Rod Mill Feed Total, by Weightometer.				Tonnage and Head Grade Reported by Mill on the Month to Date Production Summary.				Head Grade Reported by Assay Lab, from Composite Sample Taken at the Shark's fin Sampler. (mill final tonnage)					
SEPT 90	Tonnes	Pb%	Zn%	Pb+Zn	Tonnes	Pb%	Zn%	Pb+Zn	DMT	Pb%	Zn%	Pb+Zn	DMT	Pb%	Zn%	Pb+Zn	Pb+Zn	Pb+Zn
1	12,237	3.34	5.81	9.15	12,640	2.97	4.93	7.90	12,450	3.18	4.99	8.17	12,450	3.18	4.99	8.17	0.00	1.35
2	12,237	3.34	5.81	9.15	14,653	2.35	4.15	6.50	14,463	3.02	4.85	7.87	14,463	3.02	4.85	7.87	0.00	1.49
3	12,237	3.34	5.81	9.15	14,398	2.57	4.69	7.26	14,211	2.77	4.85	7.62	14,211	2.77	4.85	7.62	0.00	1.57
4	7,170	3.20	5.21	8.41	12,708	2.94	5.22	8.16	12,479	3.15	5.54	8.69	12,479	3.15	5.54	8.69	0.00	2.05
5	7,170	3.20	5.21	8.41	4,884	3.16	5.37	8.53	4,796	3.62	5.07	8.69	4,796	3.62	5.07	8.69	0.00	3.57
6	11,280	3.22	5.29	8.51	11,047	3.01	5.23	8.24	10,937	3.24	5.54	8.78	10,937	3.24	5.54	8.78	0.00	3.40
7	13,627	2.96	5.38	8.34	8,271	2.72	4.86	7.58	13,798	3.17	5.33	8.50	13,798	3.17	5.33	8.50	0.00	
8	13,627	2.96	5.38	8.34	14,672	2.75	4.90	7.65	14,423	3.75	5.43	9.18	14,423	3.75	5.43	9.18	0.00	
9	13,627	2.96	5.38	8.34	9,925	2.77	5.08	7.85	9,707	3.39	5.16	8.55	9,707	3.39	5.16	8.55	0.00	1.37
10	10,965	2.84	5.39	8.23	14,376	2.27	5.27	7.54	14,218	2.43	5.07	7.50	14,218	2.43	5.07	7.50	0.00	0.96
11	6,525	2.88	5.22	8.10	10,149	2.45	5.22	7.67	9,946	3.15	5.29	8.44	9,946	3.15	5.29	8.44	0.00	2.09
12	8,700	2.94	5.74	8.68	10,472	2.40	5.21	7.61	10,357	2.57	5.23	7.80	10,357	2.57	5.23	7.80	0.00	0.95
13	16,550	2.28	5.23	7.51	12,463	2.56	5.72	8.28	12,426	2.65	5.42	8.07	12,426	2.65	5.42	8.07	0.00	1.79
14	11,260	3.02	5.57	8.59	14,582	2.75	5.34	8.09	14,422	2.78	5.19	7.97	14,422	2.78	5.19	7.97	0.00	1.60
15	11,260	3.02	5.57	8.59	14,601	2.72	5.16	7.88	14,528	2.74	5.15	7.89	14,528	2.74	5.15	7.89	0.00	
16	11,260	3.02	5.57	8.59	14,729	2.98	5.88	8.86	14,655	2.76	4.92	7.68	14,655	2.76	4.92	7.68	0.00	1.27
17	8,040	3.11	5.54	8.65	13,136	2.39	4.97	7.36	13,018	2.40	4.49	6.89	13,018	2.40	4.49	6.89	0.00	1.03
18	9,120	2.87	5.39	8.26	12,814	2.36	4.46	6.82	12,647	2.56	4.71	7.27	12,647	2.56	4.71	7.27	0.00	1.68
19	9,120	2.87	5.39	8.26	10,963	2.40	4.82	7.22	10,853	2.70	4.85	7.55	10,853	2.70	4.85	7.55	0.00	1.70
20	10,740	3.32	5.67	8.99	12,778	2.41	4.76	7.17	12,637	2.68	4.89	7.57	12,637	2.68	4.89	7.57	0.00	1.77
21	12,300	3.23	5.63	8.86	13,830	2.95	5.20	8.15	13,595	3.22	5.25	8.47	13,595	3.22	5.25	8.47	0.00	1.62
22	12,300	3.23	5.63	8.86	13,360	2.99	5.71	8.70	13,120	3.05	5.30	8.35	13,120	3.05	5.30	8.35	0.00	1.66
23	12,300	3.23	5.63	8.86	13,314	2.95	5.34	8.29	13,128	3.03	5.34	8.37	13,128	3.03	5.34	8.37	0.00	1.98
24	10,440	3.23	5.55	8.78	11,936	3.07	5.18	8.25	13,269	3.24	5.81	9.05	13,269	2.91	4.94	7.85	1.20	2.25
25	10,440	3.23	5.55	8.78	14,982	3.01	5.10	8.11	14,832	3.16	5.21	8.37	14,832	3.16	5.21	8.37	0.00	1.83
26	15,720	3.44	5.80	9.24	14,336	2.43	4.71	7.14	14,064	2.65	5.12	7.77	14,064	2.65	5.12	7.77	0.00	1.58
27	7,065	3.16	4.82	7.98	14,508	2.56	4.41	6.97	14,334	3.03	5.10	8.13	14,334	3.59	6.04	9.63	-1.50	1.28
28	11,403	3.77	6.05	9.82	14,118	2.88	4.88	7.76	13,864	3.13	5.24	8.37	13,864	3.13	5.24	8.37	0.00	1.51
29	11,403	3.77	6.05	9.82	14,575	2.81	3.90	6.71	14,356	3.11	5.21	8.32	14,356	3.11	5.21	8.32	0.00	1.26
30	11,403	3.77	6.05	9.82				0.00				0.00	0	2.50	4.65	7.15	-7.15	1.59
31				0.00				0.00				0.00	0			0.00	0.00	
MTD:	331,524	3.16	5.57	8.72	369,220	2.70	5.01	7.71	371,532	2.96	5.16	8.12	371,532	2.97	5.16	8.13	-0.240	1.710 % avg. daily tails
		Pb+Zn=		8.72 %		Pb+Zn=		7.71 %		Pb+Zn=		8.12 %			Pb+Zn=	8.13	avg. daily adjustment by mill	78.96 % mill efficiency
																		21.03 % loss

Variance Percentage:	tonnes	%Pb	%Zn	Pb+Zn
Geology vs D.S.A	-11.37%	14.36%	10.03%	11.59%
Geology vs Mill Final	-12.07%	6.15%	7.36%	6.92%
Geology vs 24 hour Composite	-12.07%	5.84%	7.26%	6.75%
Mill Final vs 24 Hour Comp.	n/a	-0.33%	-0.10%	-0.18%

Truck count factor: 1.113705
Moisture content: -0.626 %

* Sample not available