

File= HEADCOMP.WR1
Bern. disk#8 \CURRENT
03-Jan-91

CURRAGH RESOURCES INC.
GEOLOGY DEPARTMENT SUMMARY REPORT
REPORTED HEADGRADE COMPARISON FROM VARIOUS SOURCES

Month	GEOLOGY				O.S.A.				MILL FINAL				24 HOUR COMPOSITE				MILL FINAL	FINAL TAILS
	Tonnage and Head Grade to CRUSHER Reported by Geology Department Each Day, Using Blasthole Data for grades and Truck Count for tonnage				Tonnage and Head Grade Reported by Mill Shift Reports Each Day, Using Average O.S.A Reading, and Rod Mill Feed Total, by Weightometer.				Tonnage and Head Grade Reported by Mill on the Month to Date Production Summary.				Head Grade Reported by Assay Lab, from Composite Sample Taken at the Shark's fin Sampler. (mill final tonnage)				vs 24 HOUR COMPOSITE	from 24 hour composite
DEC 90	Tonnes	PbZ	ZnZ	Pb+Zn	Tonnes	PbZ	ZnZ	Pb+Zn	DMT	PbZ	ZnZ	Pb+Zn	DMT	PbZ	ZnZ	Pb+Zn	Pb+Zn	Pb+Zn
1	9,929	3.38	5.30	8.68	9,138	2.61	4.28	6.89	9,037	2.28	3.86	6.14	9,037	2.22	3.74	5.96	0.18	1.24
2	9,929	3.38	5.30	8.68	13,221	2.58	4.88	7.46	13,062	2.53	4.21	6.74	13,062	2.22	3.93	6.15	0.59	1.20
3	9,929	3.38	5.30	8.68	12,349	2.39	4.79	7.18	12,250	2.55	4.62	7.17	12,250	2.55	4.62	7.17	0.00	1.40
4	9,929	3.38	5.30	8.68	10,181	2.30	4.28	6.58	10,100	3.16	4.92	8.08	10,100	3.16	4.92	8.08	0.00	1.27
5	9,929	3.38	5.30	8.68	6,543	2.09	4.77	6.86	6,445	2.85	4.72	7.57	6,445	2.85	4.72	7.57	0.00	1.96
6	9,929	3.38	5.30	8.68	13,457	2.35	4.70	7.05	13,269	3.09	5.18	8.27	13,269	2.89	4.87	7.76	0.51	1.98
7	9,929	3.38	5.30	8.68	14,915	2.55	4.60	7.15	14,840	3.09	5.06	8.15	14,840	3.09	5.06	8.15	0.00	1.78
8	9,929	3.38	5.30	8.68	13,004	2.55	4.77	7.32	12,861	2.69	4.81	7.50	12,861	2.69	4.81	7.50	0.00	1.12
9	9,929	3.38	5.30	8.68	14,298	2.62	4.90	7.52	14,126	2.95	4.87	7.82	14,126	2.95	4.87	7.82	0.00	1.09
10	9,929	3.38	5.30	8.68	13,000	3.24	3.87	7.11	12,844	4.28	5.13	9.41	12,844	4.28	5.13	9.41	0.00	1.24
11	9,929	3.38	5.30	8.68	11,580	3.58	5.15	8.73	11,476	3.85	5.01	8.86	11,476	3.85	5.01	8.86	0.00	1.45
12	9,929	3.38	5.30	8.68	5,664	3.22	5.33	8.55	5,630	2.84	5.21	8.05	5,630	2.84	5.21	8.05	0.00	1.83
13	8,400	3.80	5.98	9.78	7,942	2.99	5.36	8.35	7,894	2.60	4.47	7.07	7,894	2.60	4.47	7.07	0.00	1.47
14	8,400	3.80	5.98	9.78	5,188	3.14	4.26	7.40	5,131	3.67	4.91	8.58	5,131	5.28	4.69	9.97	-1.39	1.22
15	8,400	3.80	5.98	9.78	14,014	3.29	4.50	7.79	13,888	3.71	4.63	8.34	13,888	3.71	4.63	8.34	0.00	1.52
16	8,400	3.80	5.98	9.78	14,054	3.07	5.49	8.56	13,857	3.03	5.45	8.48	13,857	3.03	5.45	8.48	0.00	1.71
17	10,130	3.69	5.96	9.65	14,050	3.26	6.92	10.18	13,769	3.54	7.15	10.69	13,769	3.54	7.15	10.69	0.00	2.07
18	10,130	3.69	5.96	9.65	14,165	3.25	4.61	7.86	13,981	3.58	4.81	8.39	13,981	3.58	4.81	8.39	0.00	1.28
19	10,980	4.14	5.01	9.15	12,560	3.65	4.57	8.22	12,397	4.13	4.74	8.87	12,397	4.13	4.74	8.87	0.00	1.73
20	12,900	3.75	5.20	8.95	14,216	3.64	4.96	8.60	14,031	3.67	4.56	8.23	14,031	3.67	4.56	8.23	0.00	1.62
21	16,490	3.64	5.69	9.33	14,598	3.47	5.95	9.42	14,350	3.28	5.46	8.74	14,350	3.28	5.46	8.74	0.00	1.45
22	16,490	3.64	5.69	9.33	14,522	3.40	5.86	9.26	14,290	3.15	5.24	8.39	14,290	3.15	5.24	8.39	0.00	1.35
23	16,490	3.64	5.69	9.33	14,019	3.39	5.81	9.20	13,823	3.01	4.88	7.89	13,823	3.01	4.88	7.89	0.00	1.34
24	16,490	3.64	5.69	9.33	14,237	3.59	5.98	9.57	14,052	3.17	5.26	8.43	14,052	3.17	5.26	8.43	0.00	1.39
25	16,490	3.64	5.69	9.33	14,686	3.52	5.56	9.08	14,480	2.96	4.84	7.80	14,480	2.96	4.84	7.80	0.00	1.39
26	16,490	3.64	5.69	9.33	14,191	3.23	5.42	8.65	13,992	3.04	4.72	7.76	13,992	3.04	4.72	7.76	0.00	1.31
27	10,380	2.97	5.19	8.16	14,570	2.95	5.36	8.31	14,483	2.40	4.78	7.18	14,483	2.40	4.78	7.18	0.00	1.09
28	10,112	3.10	5.17	8.27	13,920	2.77	4.64	7.41	13,892	2.36	4.35	6.71	13,892	2.36	4.35	6.71	0.00	0.90
29	10,112	3.10	5.17	8.27	14,233	3.05	5.23	8.28	14,148	2.94	5.17	8.11	14,148	2.94	5.17	8.11	0.00	1.09
30	10,112	3.10	5.17	8.27	12,233	3.05	5.36	8.41	12,135	3.69	5.47	9.16	12,135	3.69	5.47	9.16	0.00	1.17
31	8,740	3.04	4.59	7.63	8,914	3.03	5.15	8.18	8,861	3.22	5.41	8.63	8,861	3.22	5.41	8.63	0.00	1.53

MTD:	345,286	3.51	5.47	8.98	383,662	3.05	5.12	8.17	379,394	3.15	4.98	8.13	379,394	3.15	4.96	8.11	-0.003	1.425 %
		Pb+Zn=	8.98 %			Pb+Zn=	8.17 %			Pb+Zn=	8.13 %			Pb+Zn=	8.11		avg. daily	avg. daily
																	adjustment	tails
																	by mill	mill efficiency
																		17.58 % loss

+ 32000t
of Coarse ore

Variance Percentage:	tonnes	%Pb	%Zn	Pb+Zn	Truck count factor:	1.111142
Geology vs O.S.A	-11.11%	12.96%	6.49%	9.02%	Moisture content:	1.113 %
Geology vs Mill Final	-9.88%	10.25%	8.93%	9.44%		
Geology vs 24 hour Composite	-9.88%	10.17%	9.41%	9.71%		
Mill Final vs 24 Hour Comp.	n/a	-0.09%	0.53%	0.29%	* Sample not available	