

000587

hole-id	comp	%Fe	%Pb	%Zn	Ag g/t	comp	SG
90F-02	bch 28	-1.00	1.30	1.24	24.6	bch 28	2.93
90F-02	bch 29	-1.00	3.03	4.76	44.1	bch 29	3.47
90F-02	bch 30	-1.00	2.24	3.65	31.4	bch 30	3.93
90F-02	bch 31	-1.00	2.53	1.85	31.1	bch 31	4.57
90F-02	bch 32	-1.00	3.34	5.11	26.3	bch 32	4.69
90F-02	bch 33	-1.00	4.87	2.52	36.2	bch 33	4.53
90F-02	bch 34	-1.00	2.89	4.45	33.0	bch 34	4.39
90F-02	bch 35	-1.00	2.38	4.68	10.0	bch 35	4.47
90F-02	bch 36	-1.00	3.82	6.18	10.0	bch 36	4.87
90F-02	bch 37	-1.00	2.94	7.21	16.1	bch 37	3.66
90F-02	bch 38	-1.00	1.18	2.51	11.8	bch 38	3.09
86F-18	bch 21	-1.00	.01	.06	.2	bch 21	2.74
86F-18	bch 22	-1.00	.60	.79	9.9	bch 22	3.80
86F-18	bch 23	-1.00	1.67	2.44	24.8	bch 23	3.27
86F-18	bch 24	-1.00	.33	1.29	20.6	bch 24	3.76
86F-18	bch 25	-1.00	.29	1.11	7.6	bch 25	3.85
86F-18	bch 26	-1.00	.45	.45	11.1	bch 26	4.08
86F-18	bch 27	-1.00	.27	1.04	6.2	bch 27	4.14
86F-18	bch 28	-1.00	.64	2.01	6.5	bch 28	4.24
86F-18	bch 29	-1.00	2.71	7.34	21.9	bch 29	4.17
86F-18	bch 30	-1.00	1.96	4.54	22.6	bch 30	3.33
86F-18	bch 31	-1.00	2.46	4.56	51.4	bch 31	2.99
86F-18	bch 32	-1.00	1.70	4.77	27.9	bch 32	3.05
86F-18	bch 33	-1.00	2.75	4.46	66.0	bch 33	3.09
86F-18	bch 34	-1.00	.68	.28	19.5	bch 34	2.85
90F-64	3650	12.73	.27	1.18	4.5	3650	3.53
90F-64	3630	18.47	.56	2.24	10.6	3630	3.51
90F-64	3610	20.71	2.13	5.96	14.7	3610	3.73
90F-81	3650	22.66	4.32	5.23	39.2	3650	4.09
90F-81	3630	13.31	2.86	3.55	31.9	3630	3.32
90F-81	3610	.00	.00	.00	.0	3610	2.70
90F-81	3590	12.37	1.59	1.08	14.5	3590	3.23
90F-81	3570	22.63	1.19	1.78	7.1	3570	3.76
90F-81	3550	20.23	1.30	1.57	12.6	3550	3.61
90F-81	3530	21.10	1.01	1.94	5.5	3530	3.66
90F-81	3510	24.53	.10	.57	2.7	3510	3.78
90F-81	3490	26.86	.55	1.60	3.4	3490	3.95
90F-81	3470	29.40	.32	1.12	3.9	3470	4.07
90F-81	3450	34.15	.13	.55	3.1	3450	4.30
90F-81	3430	30.10	.30	.53	6.6	3430	4.08
90F-81	3410	28.77	1.65	1.84	8.8	3410	4.11
90F-81	3390	24.76	2.06	4.74	5.7	3390	3.98
90F-81	3370	20.21	2.78	6.43	9.6	3370	3.80
90F-81	3350	16.62	3.54	5.61	21.1	3350	3.61
90F-81	3330	16.15	4.78	2.64	29.8	3330	3.60
90F-81	3310	13.93	1.14	2.44	18.7	3310	3.29
90F-81	3290	9.20	1.90	3.91	40.9	3290	3.11
90F-82	3610	7.78	3.90	6.36	26.3	3610	3.53
90F-82	3590	12.45	5.38	8.73	53.3	3590	3.55
90F-82	3570	12.16	4.68	9.43	40.5	3570	3.51
90F-82	3550	14.86	2.61	5.85	14.1	3550	3.48
90F-82	3530	24.16	.72	1.61	6.0	3530	3.82
90F-82	3510	24.72	.72	2.18	6.0	3510	3.86
90F-82	3490	23.04	.83	1.68	8.0	3490	3.76
90F-82	3470	25.16	.32	1.13	3.1	3470	3.84
90F-82	3450	19.73	.46	1.63	3.4	3450	3.56
90F-82	3430	22.91	.42	1.34	2.0	3430	3.72
90F-82	3410	24.80	.31	.45	3.2	3410	3.91

90F-82	3390	26.02	.66	1.63	4.3	3390	3.91
90F-82	3370	26.43	3.00	4.57	9.1	3370	4.10
90F-82	3350	26.10	5.03	2.69	18.1	3350	4.14
90F-82	3330	15.83	3.89	2.15	23.0	3330	3.52
90F-82	3310	17.33	1.97	4.48	13.7	3310	3.56
90F-82	3290	8.04	1.25	3.09	16.8	3290	2.98
90F-82	3270	.25	.01	.04	.2	3270	2.85

186081