

000677

CURRAGH RESOURCES INC.
 BLASTHOLE CALCULATED DENSITIES OF THE DRILLED AND BLASTED IN FARD PIT FROM JANUARY 1, 1990 TO JULY 24, 1996.

24-341-90

| YSMR | SG VOL (BCY) | SG TONNES | SG DEN. T/BCY | MG VOL (BCY) | MG TONNES | MG DEN. T/BCY | LG VOL (BCY) | LG TONNES | LG DEN. T/BCY | +SI VOL (BCY) | +SI TONNES | +SI DEN. T/BCY | TOTAL VOL (BCY) | TOTAL TONNES | DEN. T/BCY |
|--------|-----------------|--------------|------------------|-----------------|--------------|------------------|-----------------|--------------|------------------|------------------|---------------|-------------------|--------------------|-----------------|---------------|
| E 3778 | 2,932.6 | 9,916.7 | 3.353 | 0.0 | 0.0 | 0.004 | 0.0 | 0.0 | 0.004 | 2,933 | 9,901 | 3.353 | 2732.6 | 9100.7 | 3.353 |
| E 3730 | 3,526.7 | 11,798.5 | 3.317 | 0.0 | 0.0 | 0.040 | 0.0 | 0.0 | 0.040 | 3,557 | 11,799 | 3.317 | 3554.7 | 11798.5 | 3.317 |
| E 3730 | 0.0 | 0.0 | 0.000 | 11,731.9 | 38,187.6 | 3.252 | 170.4 | 554.6 | 3.255 | 11,732 | 38,148 | 3.252 | 11902.3 | 38702.2 | 3.252 |
| E 3710 | 0.0 | 0.0 | 0.000 | 12,579.8 | 41,287.4 | 3.282 | 272.6 | 883.1 | 3.460 | 12,580 | 41,287 | 3.282 | 12852.4 | 42250.5 | 3.286 |
| E 3690 | 7,492.4 | 25,823.5 | 3.441 | 11,126.6 | 36,744.9 | 3.302 | 1,342.1 | 4,025.0 | 2.930 | 18,619 | 61,888 | 3.319 | 19921.1 | 65623.4 | 3.294 |
| E 3470 | 14,442.9 | 44,723.6 | 3.054 | 10,195.7 | 28,352.8 | 2.744 | 3,051.1 | 8,539.2 | 2.733 | 24,859 | 79,228 | 3.187 | 27499.7 | 87566.7 | 3.138 |
| E 3450 | 0.0 | 0.0 | 0.000 | 18,325.8 | 49,329.9 | 2.744 | 12,373.3 | 33,846.5 | 2.671 | 30,320 | 80,353 | 2.746 | 22698.6 | 61397.3 | 2.705 |
| E 3410 | 11,597.0 | 33,150.0 | 2.911 | 6,739.6 | 15,175.6 | 3.189 | 0.0 | 0.0 | 0.000 | 16,356 | 48,935 | 2.945 | 16356 | 48935 | 2.993 |
| S 3390 | 11,742.0 | 33,540.0 | 2.854 | 4,329.0 | 13,739.0 | 3.174 | 0.0 | 0.0 | 0.000 | 16,071 | 47,279 | 2.942 | 16071 | 47279 | 2.942 |
| E 3350 | 26,893.6 | 76,845.6 | 2.858 | 19,979.3 | 58,788.0 | 2.938 | 977.8 | 2,488.6 | 2.545 | 49,015 | 139,779 | 2.852 | 19992.4 | 182267.4 | 2.846 |
| S 3334 | 76,839.3 | 232,488.8 | 3.026 | 22,424.0 | 66,983.9 | 2.984 | 645.2 | 1,885.9 | 2.835 | 49,320 | 143,780 | 2.925 | 49994.8 | 143665.4 | 2.914 |
| S 3310 | 113,411.7 | 345,466.5 | 3.048 | 34,770.0 | 92,686.7 | 3.017 | 2,733.6 | 8,095.8 | 2.938 | 107,539 | 325,176 | 3.023 | 110314.9 | 333272.3 | 3.021 |
| S 3294 | 187,368.5 | 646,879.9 | 3.240 | 46,433.4 | 139,976.7 | 3.014 | 16,458.0 | 50,430.0 | 3.028 | 159,847 | 485,643 | 3.036 | 176542.3 | 534072.7 | 3.037 |
| S 3476 | 174,846.0 | 576,228.5 | 3.223 | 32,543.6 | 98,446.5 | 3.028 | 19,939.6 | 59,776.1 | 2.998 | 219,852 | 705,285 | 3.208 | 239791.7 | 743061.4 | 3.191 |
| S 3458 | 155,438.2 | 519,907.2 | 3.353 | 18,425.8 | 56,355.9 | 2.972 | 13,097.9 | 38,833.4 | 2.734 | 195,466 | 625,584 | 3.200 | 208513.7 | 661917.8 | 3.171 |
| | 817,372.2 | 2,591,907.5 | 3.171 | 267,793 | 810,255 | 3.025 | 79,664 | 228,462 | 2.856 | 1,005,165 | 3,407,167 | 3.133 | 1145079 | 3630224 | 3.116 |

grades for benches 5-3490 - HG 9.17 MG 5.85 LG 4.15
 5-3470 - 8.94 5.31 3.96
 5-3450 - 9.18 5.29 3.76
 E-3690 - 8.75 5.33 3.90
 E-3670 - 10.42 5.94 4.63
 E-3650 - 4 6.12 4.52

SENT BY: Curragh Resources, Inc. : 18-26-90 : 9:47AM :

FARO Mine - CURRAGH Whitehorse : # 2