

000865

D.D.H. COMPOSITES - 1972

<u>Sample No.</u>	<u>D.D.H.</u>	<u>Interval</u>	<u>Feet</u>	<u>Fe % Insol.</u>	<u>Fe % Sol.</u>	<u>Ba %</u>
1	72 - 1	75' - 107'	32	4.6	12.8	<0.5
2		107' - 133'	26	7.1	7.0	<0.5
3	72-2	222.5' - 251.6'	29.1	16.1	17.2	<0.5
4		251.6' - 276.3'	24.7	3.2	13.3	<0.5
5	72-3	17' - 57'	40	21.0	11.3	3.0
6		57' - 97'	40	24.7	7.3	5.9
7		97' - 137'	40	28.7	5.0	4.5
8		137' - 177'	40	25.1	12.1	<0.5
9		177' - 217'	40	32.7	3.1	<0.5
10		217' - 237'	20	20.2	10.1	<0.5
11	72-6	170' - 210'	40	23.6	2.8	<0.5
12		210' - 249'	39	20.0	2.3	<0.5
13		249' - 274'	25	15.5	3.0	<0.5
14	72-7	95' - 135'	40	23.1	6.5	13.0
15		135' - 165'	30	17.8	7.8	20.0
16		165' - 190'	25	18.0	4.9	>20.0
17		335' - 370'	35	30.7	8.6	<0.5
18		370' - 410'	40	29.6	3.3	<0.5
19		410' - 430'	20	7.0	4.4	<0.5
20	72-8	185' - 225'	40	21.7	9.2	1.0
21		225' - 265'	40	30.2	4.5	<0.5
22		265' - 305'	40	35.1	4.0	<0.5

Note: Fe_{insol.} % and Fe_{sol.} % are meant to roughly approximate % pyrite and pyrrhotite respectively.