

SW Under ground.

Drilled

Holes	% Pb	% Zn	g/t Ag	Pb+Zn	Thickness
✓ 70-13	4.87	8.08 ✓	53.20 ✓	12.95	8.0'
✓ 71-04	3.55	5.70 ✓	NA ✓	9.25	10.00'
✓ 71-05	3.72	5.29 ✓	61.26 ✓	9.01	26.5'
✓ 71-05 (10')	5.46	5.80	77.60	11.26	10.'
✓ 72-13	6.69	6.85 ✓	82.47 ✓	13.54	45'
✓ 82F-10	5.11	8.09 ✓	81.52 ✓	13.20	13.2'
✓ 82F-12 (13.5')	3.25	5.22 ✓	43.82 ✓	8.47	13.5'
✓ 82F-12 (9.2')	3.80	6.27	44.91	10.07	9.2'
✓ 75456-15	4.94	7.90 ✓	55.60 ✓	12.84	20'
✓ 82F-14	5.24	7.43 ✓	78.27 ✓	12.67	30.8'
✓ 82F-15 (14.9')	3.14	5.51 ✓	46.10 ✓	8.65	14.9'
✓ 82F-15 (14.7')	3.48	5.74	51.30	9.32	14.7'
✓ 82F-16	5.84	7.86 ✓	88.88 ✓	13.70	14.5'
✓ 83F-02 (34.3')	4.7	6.02	74.12	10.72	34.3'
⇒ 83F-02 (36.1')	4.55	6.02	71.27	10.57	36.1'
✓ 83F-12	4.22	8.02 ✓	64.78 ✓	12.24	18.9'
✓ 83F-15	4.13	7.39 ✓	70.02 ✓	11.52	17.1'
✓ 83F-19	6.09	11.35 ✓	87.38 ✓	17.44	30.1'
✓ 88F-11	4.68	7.46 ✓	81.50 ✓	12.14	20.2'
✓ 88F-13	5.46	6.12 ✓	91.33 ✓	11.58	7.5'
✓ 88F-14 Top (3435' to 357')	3.85	6.34 ✓	44.06 ✓	10.19	13.5'
✓ 88F-14 Bottom (3675' to 4030')	5.21	8.28	61.41 ✓	13.49	35.5'
✓ 88F-15	5.35	7.26 ✓	65.85 ✓	12.61	26.5'
✓ 88F-16	3.63	7.13 ✓	64.96 ✓	10.76	11.5'

ASSAY LOG (SAMPLER'S COPY)

Date May 2nd/89

Logged by M. Wasek

Sampled by M. Wasek

CODE	FROM		TO		SAMPLE	INTR.	REC (m)	UNIT	DESCRIPTION								
	10	14	16	20					22	26	28	30	32	34	36	40	42
	1331	135	1335	135	426176	140	1	2A103	0.55	0.24	0.31	4					
	1335	135	1339	130	426177	135	1	2A103	2.52	0.64	1.88	6					
	1339	130	1343	135	426178	145	1	2D45	3.60	0.39	3.21	8					
	1343	135	1340	135	426179	130	1	2F4	18.60	6.50	12.1	38					
	1346	135	1350	135	426180	140	1	2A103	3.22	1.56	1.66	22					
	1350	135	1353	130	426181	125	1	2F4	11.47	3.92	7.55	48					
	1353	130	1357	130	426182	140	1	2H34	10.05	4.11	5.94	68					
	1357	130	1361	130	426183	140	1	2F4	5.38	1.07	4.31	26					
	1361	130	1365	130	426184	140	1	1D149	5.45	1.45	4.00	28					
	1365	130	1367	135	426185	125	1	1D149	1.51	0.64	0.97	14					
	1367	135	1371	130	426186	135	1	2H34	12.55	5.32	7.23	88					
	1371	130	1374	130	426187	130	1	2H34	13.39	5.65	7.74	82					
	1374	130	1377	130	426188	130	1	2H34	16.36	6.63	9.73	92					
	1377	130	1382	130	426189	150	1	2F4	13.54	4.75	8.79	60					
	1382	130	1387	130	426190	150	1	2F4	13.67	5.08	8.59	16					
	1387	130	1390	130	426191	130	1	2F4	15.98	6.76	9.22	74					
	1390	130	1393	130	426192	130	1	2F4	14.08	5.16	8.92	24					
	1393	130	1394	130	426193	110	1	1D49	5.22	2.91	2.37	10					
	1394	130	1399	130	426194	150	1	2H34	12.44	4.55	8.39	74					
	1399	130	1403	130	426195	140	1	2H34	12.43	4.74	7.69	74					
	1403	130	1407	130	426196	140	1	2A0	6.48	1.77	4.71	34					
	1407	130	1412	130	426197	150	1	2A0	3.16	0.93	2.23	22					
	1412	130	1417	130	426198	150	1	2A0	1.88	0.97	1.01	26					
	1417	130	1422	130	426199	150	1	2A0	2.57	1.57	1.00	40					
	1422	130	1427	130	42700	150	1	2A0	1.99	0.51	1.48	14					
	1427	130	1432	130	42701	150	1	2A0	1.66	0.60	1.06	14					

DDH: 70-13 UTM-N: 7561.2 UTM-E: 14814.0 UTM-ELEV: 4011.2 TOTAL DEPTH: 706.0 SECTION:
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

---DEPTHS---		SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													
FROM	TO					Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %
400.0	463.5	71582	63.5	.0 ****	2.75														
463.5	467.0	71583	3.5	.0 2B0	2.79	.01	.03	.14	1.50				6	13	19	.31		.15	
467.0	471.0	71584	4.0	.0 2B0	3.32	.25	.88	1.72	13.20				6	13	19	.11		.15	
471.0	475.0	71585	4.0	.0 2D4	3.49	.10	3.28	8.82	25.20				6	13	19	.06		.15	
475.0	479.0	71586	4.0	.0 2G0	4.66	.12	6.46	7.34	81.20				6	13	19	.10		.15	
479.0	483.0	71587	4.0	.0 2A0	2.84	.04	.76	1.72	16.30				6	13	19	.73		.15	
483.0	488.0	71588	5.0	.0 2A0	2.81	.06	.90	2.28	18.20				3	3	7	.45		.05	
488.0	493.0	71589	5.0	.0 2A0	2.84	.05	.39	.64	9.60				3	3	7	.45		.05	
493.0	498.0	71590	5.0	.0 2A0	2.70	.04	.68	1.08	14.60				3	3	7	.60		.05	
498.0	503.0	71591	5.0	.0 2A0	2.72	.04	.51	.82	13.60				3	3	7	.51		.05	
528.0	531.5	71593	3.5	.0 2B4	2.98	.03	6.71	5.15	180.00				3	1	5	.04		.07	
531.5	535.0	71594	3.5	.0 2B0	2.89	.05	5.38	.39	115.50				3	1	5	.14		.07	

4.87
6.08
4.8

Handwritten scribbles and marks on the right side of the page, including wavy lines and the letter 'W'.

Handwritten scribble at the bottom right of the page.

DDH: 71-04 UTM-N: 7983.0 UTM-E: 14402.0 UTM-ELEV: 3992.6 TOTAL DEPTH: 570.0 SECTION: 124
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

							-----ASSAYS-----															
DEPTHS		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu	Pb	Zn	Ag(AA)	Ag(FA)	Au(FA)	Po	Py	TOT	BaO	Hg	Mn	As	Ba	S.G.	
FROM	TO						%	%	%	g/mT	g/mT	g/mT	%	%	Fe	%	%	%	%	%	%	%
504.0	509.0	71667	5.0	.0	2A0	.50		.50	1.60													
509.0	514.0	71668	5.0	.0	2A4	.50		2.10	3.60													
514.0	519.0	71669	5.0	.0	2A0	.50		.60	1.60													
519.0	524.0	71670	5.0	.0	2A4	.50		1.90	2.90													
524.0	529.0	71671	5.0	.0	2E4	.50		3.20	5.60													
529.0	534.0	71672	5.0	.0	2E4	.50		3.90	5.80													
534.0	539.0	71673	5.0	.0	2E4	.50		6.00	1.40													
539.0	544.0	71674	5.0	.0	2E4	.50		1.30	6.00													
544.0	548.0	71675	4.0	.0	2E4	.50		1.10	6.80													

4.37 4.27

15.0

DDH: 71-05 UTM-N: 7721.0 UTM-E: 14596.0 UTM-ELEV: 4001.5 TOTAL DEPTH: 567.0 SECTION: 126
RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

DEPTHS				ASSAYS																
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Pd %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
514.0	517.5	71683	3.5	.0	2A0	3.04	.32	1.79	.55	69.30			5	18	23	.14				.21
517.5	522.5	71684	5.0	.0	2F4	4.05	.18	5.75	6.11	71.60		.27	5	18	23	.64				.21
522.5	527.5	71685	5.0	.0	2F4	4.61	.18	5.18	5.49	83.60		.27	5	18	23	6.80				.21
527.5	533.0	71686	5.5	.0	200	2.99	.17	2.46	4.08	57.10		.62	5	18	23	1.29				.21
533.0	536.0	71687	3.0	.0	2DE	3.66	.15	3.98	4.86	76.30		.14	5	7	12	.08				.09
536.0	540.0	71688	4.0	.0	200	2.94	.18	2.56	5.27	36.80		.27	5	7	12	.75				.09
540.0	544.0	71689	4.0	.0	2D0	3.04	.15	2.06	6.03	39.30		.21	5	7	12	.69				.09
544.0	549.0	71690	5.0	.0	2A4	2.94	.07	1.83	3.53	36.80		.14	5	7	12	.20				.09
549.0	555.0	71691	6.0	.0	2A4	2.90	.08	1.67	4.22	34.40		.21	3	3	6	.24				.04
555.0	560.0	71692	5.0	.0	2A4	2.89	.11	3.54	4.48	60.70		.27	3	3	6	.22				.04
560.0	565.0	71693	5.0	.0	2A0	2.69	.08	.89	3.09	26.30		.27	3	3	6	.26				.04

3.72 5.29 61.26 265
4.01

DDH: 72-13 UTM-N: 7571.6 UTM-E: 14463.6 UTM-ELEV: 4002.0 TOTAL DEPTH: 680.0 SECTION: 126
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHO CALC: 1 SS CALC: 0

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	ASSAYS													S.G. W.R.
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	CaO %	Hg %	Mn %	As %	
577.0	582.0	71845	5.0	.0	2C0	2.94	.21	.70	.95	16.10				5	15	20	.30		.12	
582.0	587.0	71846	5.0	.0	2E4	4.07	.19	8.53	6.63	80.40				5	15	20	11.63		.12	
587.0	592.0	71847	5.0	.0	2F4	4.12	.11	5.75	9.60	58.30				.27	5	15	20	5.06		.12
592.0	597.0	71848	5.0	.0	2B4	3.32	.16	4.87	6.96	56.80				2.61	8	19	27	2.03		.27
597.0	602.0	71849	5.0	.0	2F4	4.56	.19	6.18	6.55	30.0				.21	8	19	27	6.35		.27
602.0	607.0	71850	5.0	.0	2F4	4.88	.13	6.28	6.53	87.40				.62	8	19	27	6.87		.27
607.0	612.0	71851	5.0	.0	2F4	4.11	.16	4.97	7.12	74.10				.14	8	19	27	1.70		.27
612.0	617.0	71852	5.0	.0	2B4	3.30	.25	5.30	5.88	71.20				.21	6	9	16	.77		.12
617.0	622.0	71853	5.0	.0	2F4	3.98	.34	6.95	9.55	91.20				.21	6	9	16	.31		.12
622.0	627.0	71854	5.0	.0	2B4	3.04	.07	11.39	2.83	192.80				.27	6	9	16	.10		.12
627.0	632.0	71855	5.0	.0	1D4	2.73	.08	.80	.25	16.50				6	9	16	.26		.12	
632.0	637.0	71856	5.0	.0	104	2.70	.06	.36	.10	5.90				4	4	8	1.07		.05	
637.0	642.0	71857	5.0	.0	2B4	3.04	.11	4.00	3.90	86.10			.07	4	4	8	4.59		.05	
642.0	647.0	71858	5.0	.0	2B0	2.77	.08	.62	1.37	16.20				4	4	8	.27		.05	
666.5	669.0	71860	2.5	.0	2A3	2.81	.10	.81	1.59	15.50				3	6	10	.08		.26	
669.0	673.5	71861	4.5	.0	1014	2.75	.10	1.81	1.53	17.30			.01	3	6	10	.26		.26	
673.5	678.0	71862	4.5	.0	2A0	2.62	.09	.57	1.50	11.30				3	2	6	.26		.04	

DDH: 82F-10 UTM-N: 7792.2 UTM-E: 14389.4 UTM-ELEV: 3940.6 TOTAL DEPTH: 627.0 SECTION: 125
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													S.G. W.R.
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	
517.2	519.7	82211	2.5	2.5	0Q9	2.96	.12	.70	2.54	18.97				6	4	11	.19		.08	
519.7	521.5	82212	1.8	1.8	2L0	2.84	.09	.12	.09	3.73				3	3	6	.26		.04	
521.5	526.0	82213	4.5	4.5	2A0	2.77	.07	.40	.57	9.64				2	2	5	.32		.04	
526.0	530.5	82214	4.5	4.3	2A0	2.83	.10	1.33	3.59	23.33				.07	3	2	6	.18	.03	
530.5	533.4	82215	2.9	2.9	2E46	4.03	.19	4.82	6.77	79.63				.14	8	14	22	1.41	.04	
533.4	536.6	82216	3.2	3.2	2E46	4.26	.07	4.97	9.14	65.32				.04	3	19	22	2.23	.08	
536.6	539.8	82217	3.2	3.2	2E4	4.24	.13	5.50	9.77	78.07				.04	3	19	22	.29	.09	
539.8	541.9	82218	2.1	2.1	2D06	2.99	.16	4.51	5.41	89.58				.04	3	3	6	1.12	.06	
541.9	543.7	82219	1.8	1.8	2H4	4.08	.36	5.85	8.51	110.11				.07	26	5	32	.96	.08	
543.7	548.8	82220	5.1	5.1	2A0	2.89	.06	.97	1.75	21.77				.04	4	3	7	.24	.04	
548.8	553.9	82221	5.1	5.1	2A0	2.89	.10	.51	1.17	22.39					3	3	7	.20	.01	
553.9	556.9	82222	3.0	3.0	2A0	2.80	.01	.70	1.35	23.33					2	1	3	.23	.01	
566.4	570.2	82223	3.8	3.8	2A1	2.76	.03	.57	.98	15.86					3	3	6	.23	.04	
570.2	574.1	82224	3.9	3.9	2A1	2.87	.05	.88	1.83	16.49					3	3	6	.18	.03	

**THIS REPORT WAS REQUESTED BY: LEEP .GEOLOGY AT: 10:51:17

DDH: 82F-12 UTM-N: 7283.0 UTM-E: 14897.5 UTM-ELEV: 3875.4 TOTAL DEPTH: 451.0 SECTION: 130
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

DEPTHS		SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	ASSAYS													
FROM	TO					Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %
335.2	340.0	82243	4.8	4.6	2E4	3.28	.12	4.22	8.01	52.88	.10	4	9	13	.07		.11		
340.0	344.4	82244	4.4	4.4	2DA0	2.88	.06	3.35	4.38	46.66	.04	2	2	5	.11		.07		
344.4	348.7	82245	4.3	4.3	2DA0	2.96	.05	2.07	2.95	30.79	.04	4	2	6	.40		.05		
348.7	353.0	82246	4.3	4.3	2DA0	2.92	.05	1.91	3.30	26.13	.04	3	2	6	.29		.06		
353.0	357.3	82247	4.3	4.3	2CA0	2.82	.06	.94	2.13	16.80	.04	5	2	7	.55		.07		
357.3	361.9	82248	4.6	4.2	2H0	4.02	.32	2.39	4.42	42.92	.04	26	6	32	.32		.08		
361.9	366.9	82249	5.0	5.0	2D5	2.97	.13	1.54	2.85	29.55	.04	5	4	9	.44		.04		

DDH: 82F-14 UTM-N: 7517.5 UTM-E: 14524.1 UTM-ELEV: 3992.1 TOTAL DEPTH: 700.0 SECTION: 127
RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	ASSAYS													S.G. W.R.
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	
550.8	555.7	82257	4.9	4.9	2A1	2.98	.12	.32	.65	7.47				3	7	11	.12		.03	
555.7	560.6	82258	4.9	4.9	2A0	3.15	.07	1.28	2.02	12.44				.21	2	9	12	.08	.01	
560.6	565.5	82259	4.9	4.9	2A41	2.95	.06	1.27	3.46	14.93				.82	2	7	9	.17	.03	
565.5	569.4	82260	3.9	3.9	2F48	4.35	.09	5.40	9.53	61.90				.04	5	21	26	.08	.12	
569.4	573.2	82261	3.8	3.8	2F48	4.64	.11	5.15	6.06	78.38				.10	6	25	31	1.21	.21	
573.2	578.1	82262	4.9	4.9	2F46	4.37	.16	4.52	6.50	71.54				.14	7	21	28	3.62	.27	
578.1	583.0	82263	4.9	4.9	2F46	4.49	.18	4.78	5.53	77.76				.17	8	20	29	4.82	.30	
583.0	587.6	82264	4.6	4.6	2H42	4.27	.36	6.46	8.28	104.82				.10	22	10	32	.69	.21	
587.6	592.0	82265	4.4	4.4	2E48	4.26	.21	4.89	7.18	76.83				.07	8	18	27	3.07	.21	
592.0	596.3	82266	4.3	4.3	2E48	4.31	.54	5.57	9.33	74.34				.04	5	19	25	2.06	.11	
596.3	600.3	82267	4.0	4.0	2A4	2.95	.10	1.90	3.08	29.86				.04	5	3	9	.25	.07	
608.5	614.0	82268	5.5	5.5	2B5	2.91	.07	.96	2.34	18.35				.04	4	1	6	.18	.03	
618.7	624.4	82269	5.7	5.7	2A0	2.90	.05	.65	1.06	14.31				.04	3	2	6	.17	.17	
624.4	630.1	82270	5.7	5.3	2A0	2.88	.07	1.47	1.41	36.08				.04	3	2	6	.30	.41	
630.1	635.7	82271	5.6	5.6	2A4	2.94	.09	3.78	3.02	83.05				.14	3	2	5	.26	.06	
635.7	641.3	82272	5.6	5.6	2A4	3.03	.14	1.78	4.30	40.44				.41	7	3	10	.34	.04	
641.3	646.9	82273	5.6	5.6	2A0	2.14	.06	1.18	.83	24.88				.04	4	1	5	.57	.18	

DDH: 82F-15 UTM-N: 7087.1 UTM-E: 14693.1 UTM-ELEV: 4025.6 TOTAL DEPTH: 740.0 SECTION: 130
RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

---DEPTHS---		SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	ASSAYS													
FROM	TO					Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %
590.3	595.5	82274	5.2	5.0	2LHA*	3.39	.51	.45	.52	23.02				10	11	21	.11		.03
595.5	598.4	82275	2.9	2.8	2D0	3.28	.13	2.39	7.46	26.44				.41	2	11	13	.07	.05
598.4	601.2	82276	2.8	2.8	2A1	2.28	.09	2.03	5.78	28.93				.07	1	7	8	.16	.01
601.2	605.2	82277	4.0	3.8	2E4	4.81	.16	4.34	4.86	60.65				.17	5	27	32	.96	.19
605.2	609.3	82278	4.1	4.1	2E4	3.16	.11	4.08	5.27	64.99				.10	5	26	31	3.99	.14
609.3	610.2	82279	.9	.9	2H2	4.22	.54	4.99	6.26	97.04				.17	19	10	29	4.65	.35
610.2	615.4	82280	5.2	5.2	2A4	2.22	.09	2.18	4.85	31.42				.07	6	1	7	.47	.05
615.4	620.6	82281	5.2	5.2	2A4	3.00	.12	1.85	3.62	32.04				.04	4	3	8	.30	.03
620.6	625.7	82282	5.1	4.7	2A0	2.93	.11	.94	1.78	27.99				.07	4	4	8	.55	.03
625.7	630.8	82283	5.1	5.1	2A4	2.28	.09	1.46	4.29	31.42				.04	6	3	9	.26	.04
630.8	635.9	82284	5.1	4.8	2A0	2.86	.07	.91	1.84	19.91				.07	4	2	7	.32	.02
635.9	641.0	82285	5.1	5.1	2A0	2.23	.07	.98	2.53	24.26				.04	6	1	7	.35	.03
641.0	646.1	82286	5.1	5.1	2A4	2.99	.09	1.70	4.22	32.66				.07	9	1	11	.37	.04
646.1	651.2	82287	5.1	5.1	2A0	2.15	.08	.50	.93	15.24				.04	3	2	6	.49	.05
672.0	676.5	82288	4.5	4.5	2A1	2.25	.07	.88	1.86	14.00				.04	5	4	9	.24	.06
676.5	681.0	82289	4.5	4.1	2A41	2.62	.18	2.71	6.50	53.50				.07	10	13	23	.12	.03

DDH: 82F-16 UTM-N: 7390.8 UTM-E: 14399.0 UTM-ELEV: 4004.4 TOTAL DEPTH: 707.0 SECTION: 127
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----						-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
631.0	635.1	82290	4.1	2A0	2.17	.08	.47	.65	9.64				4	3	8	.17				.08
635.1	639.2	82291	4.1	2A0	2.73	.05	.15	.19	7.15				2	3	5	.51				.17
639.2	643.3	82292	4.1	2A4	2.79	.06	1.44	2.70	37.32				.41	2	3	.19				.03
643.3	645.5	82293	2.2	2G4	4.15	.05	3.35	7.37	48.43				.17	2	12	15	20.77			.09
645.5	649.6	82294	4.1	2E4	4.06	.29	5.68	8.11	89.58				.07	12	17	29	.68			.20
649.6	653.7	82295	4.1	2E4	4.32	.15	5.82	8.36	87.40				.04	6	20	27	.20			.23
653.7	657.8	82296	4.1	2E4	4.36	.20	7.36	7.38	111.35				.07	7	21	29	.30			.18
657.8	662.0	82297	4.2	2A4	2.77	.06	1.50	3.21	27.68				.34	2	4	6	.15			.01
662.0	666.3	82298	4.3	2A0	2.77	.02	.63	1.62	12.44				.14	1	2	4	.14			.01
666.3	670.6	82299	4.3	2A0	2.81	.05	1.26	2.54	30.79				.21	3	3	7	.45			.01
670.6	676.4	82300	5.8	2A47	3.80	.36	3.15	6.34	79.00				.04	30		30	.06			.04
676.4	682.0	82301	5.6	2A0	2.74	.05	.60	1.23	16.17					3	2	5	.15			.03

DDH: 83F-02 UTM-N: 6577.2 UTM-E: 14564.5 UTM-ELEV: 4023.0 TOTAL DEPTH: 893.0 SECTION: 132+00E
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	ASSAYS													
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %
721.6	723.7	82355	2.1	2.1	2A3	3.10	.20	.35	1.70	11.20			.33	7	8	16	.20		.04	
723.7	726.3	82356	2.6	2.6	2A4	3.00	.14	2.18	4.50	38.88			.21	4	5	10	.19		.02	
726.3	728.3	82357	2.0	2.0	2A0	2.80	.05	1.26	1.85	42.30			.90	1		2	.68		.02	
728.3	730.4	82358	2.1	2.1	2H46	4.20	.21	5.32	8.12	88.33			.16	17	10	28	5.98		.14	
730.4	737.0	82359	6.6	6.6	2E64	4.10	.10	4.29	6.78	61.90			.09	5	17	22	4.94		.10	
737.0	738.4	82360	1.4	1.4	2Q48	3.52	.38	4.88	3.11	87.40			.22	6	10	17	3.33		.11	
738.4	739.9	82361	1.5	1.3	2E46	4.46	.08	5.83	6.64	92.69			.11	4	22	26	5.85		.22	
739.9	743.0	82362	3.1	3.1	2D6	3.29	.10	2.92	4.72	42.61			.12	3	9	12	5.25		.06	
743.0	745.7	82363	2.7	2.6	2D64	3.52	.19	6.09	4.54	111.04			.38	4	11	15	12.05		.09	
745.7	749.9	82364	4.2	4.2	2G4	4.51	.22	4.64	5.80	67.81			.12	5	19	24	12.15		.22	
749.9	751.6	82365	1.7	1.7	2D36	4.15	.24	3.25	4.27	56.92			.17	5	16	22	15.74		.28	
751.6	755.6	82366	4.0	4.0	2G4	4.58	.22	4.72	4.99	84.91			.21	6	21	27	6.36		.27	
755.6	759.3	82367	3.7	3.4	2G4	4.67	.17	5.56	6.31	94.87			.18	6	19	26	8.98		.26	
759.3	762.6	82368	3.3	3.3	2E41	4.23	.09	4.91	8.67	55.36			.20	5	20	26	.22		.07	
762.6	764.4	82369	1.8	1.7	2D5	3.01	.08	1.69	5.93	17.11			.20	3	3	7	.27		.06	
764.4	769.4	82370	5.0	4.9	2A41	2.87	.13	1.03	2.89	21.15			.20	3	4	8	.24		.03	
769.4	773.2	82371	3.8	3.8	2A41	2.79	.07	1.40	3.25	20.53			.19	3	2	6	.40		.06	
773.2	778.0	82372	4.8	4.6	2A41	2.76	.03	1.08	2.89	13.38			.20	1	3	5	.35		.03	
778.0	782.7	82373	4.7	4.7	2A41	2.78	.04	.96	2.61	17.11			.21	1	6	7	.31		.04	
782.7	787.0	82374	4.3	4.3	2A0	2.76	.02	.74	1.88	12.13			.19	1	1	2	.40		.01	
787.0	791.9	82375	4.9	4.3	2A0	2.66	.02	1.30	2.46	23.02			.13	2		3	.27		.04	

**THIS REPORT WAS REQUESTED BY: LEEP .GEOLOGY AT: 11:18:40

DDH: 83F-12 UTM-N: 6860.6 UTM-E: 14280.4 UTM-ELEV: 4004.7 TOTAL DEPTH: 832.0 SECTION: 127+300E
 129100 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													S.G. W.R.
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	
736.6	738.6	82431	2.0	2.0	2H41	3.89	.19	5.12	8.79	82.11		.14	13	14	28	.40		.13		
738.6	742.2	82432	3.6	3.4	2E41	4.22	.11	5.50	9.53	81.49		.13	7	22	29	.18		.11		
742.2	744.2	82433	2.0	2.0	2E48	3.96	.11	4.66	8.69	74.65		.13	4	21	26	.43		.09		
744.2	748.0	82434	3.8	3.5	2E4	4.25	.17	4.37	8.05	65.01		.12	7	23	30	.59		.27		
748.0	752.2	82435	4.2	4.2	2E4	3.87	.14	3.94	7.63	62.52		.25	6	19	25	.27		.13		
752.2	755.5	82436	3.3	3.3	2A34	3.19	.05	2.20	5.96	32.66		.41	3	10	14	.32		.04		
755.5	760.0	82437	4.5	3.1	2A34	2.94	.11	2.03	3.41	52.25		.65	4	4	9	.32		.04		
760.0	764.7	82438	4.7	4.2	2A34	2.79	.13	1.26	3.15	37.64		1.60	3	12	15	.26		.03		

Handwritten scribbles and marks at the bottom right of the page.

DDH: 83F-15 UTM-N: 7078.3 UTM-E: 14504.0 UTM-ELEV: 4013.0 TOTAL DEPTH: 759.0 SECTION: 127+300E
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

DEPTHS		SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	ASSAYS													
FROM	TO					Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %
641.4	647.0	82451	5.6	2A4	2.94	.11	2.36	3.95	29.24		.27	3	3	7	.20		.02		
647.0	652.7	82452	5.7	2D0	2.90	.10	3.88	2.08	50.08		.55	3	2	5	.32		.02		
652.7	654.8	82453	2.1	2E46	4.33	.03	4.34	12.32	59.41		.14	2	24	27	4.60		.05		
654.8	660.6	82454	5.8	2G41	4.28	.12	4.55	7.50	74.65		.09	5	16	22	14.17		.20		
660.6	662.3	82455	1.7	2D4	3.72	.17	4.78	5.08	67.50		.19	9	9	18	10.53		.15		
662.3	666.5	82456	4.2	2F46	3.84	.19	4.49	6.85	87.10		.23	9	16	25	4.03		.16		
666.5	669.8	82457	3.3	2E48	4.51	.10	2.48	5.96	48.21		.10	7	28	36	.19		.05		
669.8	675.2	82458	5.4	2A41	3.03	.05	1.74	4.41	24.37		.12	4	3	7	.36		.02		
675.2	680.5	82459	5.3	2A41	2.81	.06	1.07	2.88	21.15		.14	3	2	6	.27		.01		
680.5	684.0	82460	3.5	2A38	2.90	.10	1.06	2.51	29.55		.27	2	5	7	.25		.01		
684.0	687.4	82461	3.4	2A0	2.82	.05	.53	1.75	9.95		.05	3	2	5	.24		.01		
687.4	689.4	82462	2.0	2A1	2.75	.06	.52	1.55	15.55		.08	3		3	.22		.02		
689.4	692.6	82463	3.2	2D5	2.87	.05	.97	2.73	24.26		.04	5	2	8	.28		.04		
692.6	695.7	82464	3.1	2D5	3.09	.14	1.60	3.50	34.34		.05	8	6	14	.35		.03		
695.7	700.0	82465	4.3	2A1	2.79	.05	.80	2.02	17.42		.04	2	2	4	.21		.01		
700.0	704.3	82466	4.3	2A1	2.82	.06	.91	2.04	29.55		.05	3	2	6	.20		.04		
704.3	708.6	82467	4.3	2A1	2.78	.03	.66	2.08	15.55		.04	2	1	3	.34		.02		
708.6	709.7	82468	1.1	2C0	2.85	.05	.62	.77	18.35		.05	3	3	7	.26		.13		

W
 W
 W