

002032

31/7/710.000000
0.000000
0.000000
0.000000ORE BENCH 3910

PORTION OF BENCH MINED TO JULY 31/71

ORE BLOCK	ORIGINAL D.D. HOLE DATA				BLAST HOLE DATA				
	<u>Pb</u>	<u>Zn</u>	<u>COMB</u>	<u>TONNAGE</u>	<u>Pb</u>	<u>Zn</u>	<u>COMB</u>	<u>EST TONNAGE</u>	
- 66-12	6.8	9.7	16.5	218,485	5.1	7.6	12.7	171144	98
- 66-16	7.0	8.9	15.9	188,445	4.4	7.0	11.4	244385	100
- 70.6	5.2	7.3	12.5	94,222	4.9	7.2	12.1	107619	93
70.7	6.3	8.2	14.5	84,925	6.3	8.6	14.9	5231	33
* 66-44	7.3	8.6	15.9	150,021	4.8	7.5	12.3	66515	40
* 65-11	6.4	5.2	11.6	141,333	4.4	6.6	11.0	61283	51
66-15	4.4	6.7	11.1	188,445	4.3	6.9	11.2	32136	18
OUTSIDE 1/2 BENCH	-	-	-	1,065,876	4.0	6.9	10.9	59041	
TONNAGE X	6,658,637	8,468,364	15,127,002		. AVE. GRADE = $\frac{\Sigma \text{ASSAY}}{\Sigma \text{# HOLES}}$				
AVE GRADE	6.2	7.9	14.1		4.6	7.2	11.8	TONNAGE MINED	747354

(Block Hole % of Est. Tonnage)

3910 ORE BENCH

31/7/71

ORIGINAL ORE RESERVE CALC. DATA

(July 15/70)

<u>SHA</u>	<u>Pb</u>	<u>Zn</u>	<u>CoMB</u>	<u>Tonnage</u>
✓ 66-12	6.8	9.7	16.6	218,485
✓ 66-16	7.0	8.9	15.9	188,445
✓ 70-6	5.2	7.3	12.5	94,222
✓ 70-7	6.3	8.2	14.5	84,925
✓ 66-44	7.3	8.6	15.9	150,021
✓ 65-11	6.4	5.2	11.6	141,333
✓ 66-15	4.4	6.7	11.1	188,445
	6658637.4 6.2	8468364.3 7.9	(14.1)	192 2,065,876
70-14			13.5	86,795
66-25			12.7	26,935
67-34			15.6	25,440
65-5A			9.9	210,628
66-32			11.8	112,609
70-5			10.8	94,222
70-16			12.5? (7.9)	94,222
70-2			6.0	94,222
70-4			9.7	94,222
70-9			10.2	99,515
66-24			7.6	56,118
70-1			8.8	123,085
65-4			14.1	107,746
70-3			10.5	101,386
66-14			10.8	94,652
70-11			4.6	101,386
66-9			12.3	88,666
66-35			12.5	134,682
65-7			9.8	240,183

15,127,201.7

3052,590
3,139,012

(Ave GRADE 11.7)

86477

D.D. Hole OUTSIDE 1/2 BENCH Grade Pb Zn Comb. Tons

Blast	Hole	Pb	Zn
	7591	5.5	3.2
	75		
	99	1.6	3.4
	7606	6.2	9.0
	7916	6.0	8.8
	17	3.9	5.8
	18	5.3	8.9
	26	4.7	7.9
	27	3.0	5.4
	28	5.7	7.6
	29	5.0	8.4
	30	5.3	8.2
	31	4.6	6.7
	32	3.5	6.5
	33	 	
	36	1.9	4.1
	37	4.6	8.2
	38	3.1	4.5
	39	4.3	6.3
	40	4.2	7.3
	41	3.8	6.7
Sub-Totals	1 Holes	82.2	126.9

Blast	Hole	Pb	Zn
	42	4.3	7.8
	43	1.4	4.0
	44	5.4	11.6
	45	2.4	4.0
	46	2.2	5.8
	47	4.8	9.6
	48	4.4	7.6
	8147	5.8	9.7
	48	4.9	8.5
	8374	6.8	10.3
	75	3.0	9.1
	76	4.8	9.4
	82	5.1	10.2
	83	5.8	10.5
	84	5.2	8.9
	85	6.2	10.7
	86	2.8	7.9
	8396	5.4	10.1
	97	3.9	7.5
	98	2.6	3.9
	99	1.6	5.4
	840		
Sub-Totals	2 Holes	88.8	172.5

Blast	Hole	Pb	Zn
	8401	2.5	4.0
	02	2.5	4.5
	03	2.0	4.5
	04	5.8	8.2
	05	5.1	7.7
	10	2.4	4.3
	11	5.8	8.9
	12		
	13	3.2	6.3
	8479	3.5	4.4
	80	4.1	7.4
	81		
	82	1.8	5.2
	83	2.2	4.5
	84	3.2	5.4
	85	7.4	1.6
	86	2.6	4.9
	87	2.9	5.1
	88		
	89		
	90	2.6	5.1
	91		
	92	2.5	5.4
Sub-Totals	3 Holes	62.1	97.4

Average Pb 4.0 Zn 6.9 Combined 10.9

Actual Tons Ore Mined

Page Total	Holes	Pb	Zn
1	19	82.2	126.9
2	21	88.8	172.5
	58	253.1	396.8
	19	79.1	131.7
	77	312.2	528.5

Remarks:

ORE ~~TEST~~ COMPARISON SHEET

3910 Bench

Date 3/7/81

D.D. Hole _____

Grade Pb _____ Zn _____

Comb. _____

Tons _____

Blast Hole	Pb	Zn
8623	5.9	8.2
24	3.2	5.0
25	1.7	3.5
8808	5.2	9.7
09	4.1	8.2
10	4.2	7.4
11	3.7	6.2
12		
13	4.4	6.9
14	3.5	6.7
15	3.1	6.1
16	3.5	5.0
17	2.4	2.9
8834	5.5	7.1
35	4.4	7.4
36	6.3	9.3
8866	4.5	8.7
67	4.8	9.1
68	4.4	7.1
69		
70	4.3	7.2
Sub-Totals	19	131.7

Blast Hole	Pb	Zn
/		
Sub-Totals	2	

Blast Hole	Pb	Zn
/		
Sub-Totals	3	
1		
2		
Page Total		

Average Pb _____ Zn _____ Combined _____

Actual Tons Ore Mined _____

Remarks:

ORE BLOCK COMPARISON SHEET

3910 Bench

1 of 4
Date 3/7/71

D.D. Hole 66-12

Grade Pb Zn Comb. Tons

Blast	Hole	Pb	Zn
	7803	4.9	6.7
	04	6.6	6.8
	7959	3.8	6.4
	60	5.3	7.7
	77	5.1	8.3
	78		
	8101	6.4	9.2
	07	6.3	8.7
	8111	5.8	7.0
	12	4.9	7.0
	13	4.7	6.5
	14	5.3	7.7
	15	5.5	7.3
	16	6.5	8.7
	17	5.1	6.9
	18	5.5	7.6
	19	4.1	5.9
	20	4.6	10.9
	21	5.8	7.2
	22	4.4	7.1
	23	3.1	5.8
Sub-Totals	1	Holes 20	103.7 149.4

Blast	Hole	Pb	Zn
	8124	4.3	6.7
	25	6.0	8.4
	26	6.9	10.0
	27	5.6	9.6
	28	5.9	10.3
	29	8.6	10.7
	32	6.9	8.3
	33	4.8	7.6
	34	5.3	8.2
	35	4.8	10.3
	36	5.4	8.2
	37	6.0	9.3
	38	6.7	9.7
	39	5.8	8.4
	40	5.3	10.0
	41	4.9	8.8
	42	5.0	9.4
	43	6.9	9.7
	44	7.0	9.6
	45		
	46	4.4	7.6
Sub-Totals	2	Holes 20	116.5 180.8

Blast	Hole	Pb	Zn
	8149	6.6	9.5
	50	4.6	8.8
	51	5.1	8.8
	52	5.3	8.5
	53	4.4	8.2
	7963	6.6	7.1
	64	5.8	7.3
	65	6.6	8.4
	66	4.7	8.1
	67	6.0	7.7
	68		
	69	6.5	7.7
	70	6.1	7.5
	71	8.0	10.9
	72	6.5	9.9
	73	7.2	9.7
	74	3.6	7.5
	75	3.5	5.6
	76	7.3	9.7
	77	6.5	9.0
	78		
	79	6.8	10.0
	80		
	81	6.4	8.1
Sub-Totals	3	Holes 21	124.1 178.0

Average Pb 5.1 Zn 7.6 Combined 12.7

Actual Tons Ore Mined

Remarks:

Page Total	Holes	Pb	Zn
1	20	103.7	149.4
2	20	116.5	180.8
	61	344.3	508.2
	65	345.4	503.7
	64	283.3	440.5
	32	160.6	231.4
	222	1133.6	1683.8

ORE BLOCK COMPARISON SHEET

Bench _____

Date 3/7/71

D.D. Hole 66-12

Grade Pb _____

Zn _____

Comb. _____

Tons _____

Blast	Hole	Pb	Zn
	7980	5.9	7.7
	81		
	8221	6.4	8.8
	22	6.9	9.8
	23	5.5	8.0
	8327	5.5	8.4
	28	6.3	9.4
	29	3.7	6.2
	30	6.2	7.5
	31	5.9	6.7
	32	2.3	4.2
	33	5.4	7.1
	34	5.4	8.3
	50	6.5	6.9
	51	5.0	5.9
	52	6.6	7.4
	8369	6.7	11.5
	70	6.9	11.9
	71	6.2	11.4
	72	6.5	11.8
	73	4.7	10.8
Sub-Totals	1 20	114.5	169.7

Blast	Hole	Pb	Zn
	77	7.2	11.0
	78	6.7	12.2
	79	6.0	10.5
	80	4.1	11.3
	81	3.4	9.7
	87	6.0	9.7
	88	5.8	9.9
	8391	5.4	8.4
	92	14.2	5.1
	93	5.3	7.8
	94	3.4	5.9
	95	5.7	8.6
	8406	4.5	7.1
	07	2.0	3.2
	08		
	09	2.6	5.5
	8414	2.2	3.3
	15	4.3	5.9
	17	4.0	5.3
	18	4.7	6.3
	19		
	20	5.6	7.9
	21	5.5	6.5
Sub-Totals	2 21	108.6	161.1

Blast	Hole	Pb	Zn
	22	6.1	7.0
	23	5.0	7.6
	24	11.0	7.6
	25	3.0	6.7
	26	5.3	8.4
	27	5.1	7.2
	28	6.8	7.7
	29	7.0	6.7
	30	6.2	7.7
	31	3.7	5.6
	32	6.1	8.3
	33	5.0	8.4
	34	4.3	6.4
	38	3.6	6.1
	39	5.8	9.6
	40	5.7	9.3
	41	4.9	7.9
	42	5.9	8.8
	8453	5.2	7.7
	58	4.5	6.1
	59	4.1	8.1
	60	2.8	4.8
	61	1.8	3.2
	82	3.4	6.0
Sub-Totals	3 24	122.3	172.9

Average Pb _____ Zn _____ Combined _____

Actual Tons Ore Mined _____

Page Total --- 65 345.4 503.7

Remarks:

ORE BLOCK COMPARISON SHEET

3910

Bench

Date 3/17/71

D.D. Hole 66-12

Grade Pb Zn

Comb. Tons

Blast	Hole	Pb	Zn
	8621	5.0	8.0
	22	6.5	9.7
	26	5.5	8.1
	27	4.9	7.4
	28	4.2	6.0
	8468	7.2	9.1
	64	6.9	9.0
	65	6.9	8.4
	66	5.3	9.9
	68	7.3	10.4
	69	6.4	9.5
	70	7.1	9.1
	71	6.5	8.6
	72	6.5	8.4
	77	6.4	9.4
	78	5.7	9.2
	8564	3.6	6.6
	8712	3.9	6.6
	14	3.1	4.8
	16	3.5	6.8
	17	2.0	3.4
Sub-Totals	1 Holes 21	114.4	169.4

Blast	Hole	Pb	Zn
	18	2.0	5.0
	19	5.4	5.0
	20	3.1	5.0
	21	4.3	8.5
	22	2.8	5.8
	23	5.3	7.7
	24	5.4	7.6
	25	4.7	7.9
	26	3.1	4.3
	27	3.1	4.1
	28	6.2	8.0
	29	1.7	4.8
	30	5.3	8.4
	31	2.7	5.8
	32	5.1	8.2
	33	5.6	8.1
	34	5.6	9.3
	35	5.5	5.9
	36	4.9	8.1
	37	5.1	7.5
	38	6.0	8.1
	39	4.8	6.6
Sub-Totals	2 Holes 21	92.3	144.7

Blast	Hole	Pb	Zn
	40	5.3	7.1
	41	5.4	6.7
	42	5.5	8.0
	43	5.7	8.2
	44	4.9	7.6
	45	3.3	6.3
	46	4.8	7.7
	47	3.7	5.9
	48	3.7	5.8
	49	4.5	5.8
	50	2.6	5.4
	51	1.6	4.0
	54	1.6	3.5
	55	2.4	4.3
	56	2.6	3.8
	8768	3.8	5.2
	69	2.1	4.5
	70	4.5	6.7
	71	1.0	4.4
	72	1.1	3.9
	73	1.5	4.4
	74	5.0	7.2
Sub-Totals	3 Holes 22	76.6	126.4
	1	21	114.4
	2	21	92.3
	---	64	283.3

Average Pb Zn Combined

Actual Tons Ore Mined

Page Total

Remarks:

ORE BLOCK COMPARISON SHEET

3910 Bench

4 of 9

Date _____

D.D. Hole 66-12

Grade Pb _____ Zn _____

Comb. _____

Tons _____

Blast	Hole	Pb	Zn
	8775	3.4	5.3
	76	3.8	6.1
	77	3.4	5.3
	78	2.7	4.1
	79	2.8	5.2
	80	2.3	5.4
	81	3.5	6.0
	82	4.0	6.6
	83	5.4	7.9
	84	4.5	7.3
	85	4.4	6.2
	86	5.6	7.2
	87	5.6	7.2
	88	5.5	6.4
	89	5.8	8.4
	90	6.1	8.6
	91	5.8	7.0
	92	4.9	7.0
	93	5.6	7.9
	94	5.7	8.2
	95	6.4	8.6
	97	6.6	8.4
Sub-Totals	1	Holes 22	98.2 150.3

Blast	Hole	Pb	Zn
	98	4.7	7.5
	99	4.2	5.8
	8802	Sample	
	01	Data Missing	
	02		
	03		
	04		
	8837	6.7	7.7
	38	6.5	7.5
	39	7.5	8.0
	40	8.3	8.7
	41		
	42		
	8862	5.7	8.8
	63	6.3	8.8
	64	6.3	9.4
	65	6.2	8.9
Sub-Totals	2	Holes 10	62.4 81.1

Blast	Hole	Pb	Zn
Sub-Totals	3	Holes 0	

Average Pb _____ Zn _____ Combined _____

Actual Tons Ore Mined _____

Page Total --- 32 | 160.6 | 231.4

Remarks:

ORE BLOCK COMPARISON SHEET

3910

Bench

Date 31/7/21

D.D. Hole 66-16

Grade Pb

Zn

Comb.

Tons

Blast Hole	Pb	Zn
7586	5.3	7.8
87	5.2	7.7
88	5.3	7.4
93	4.8	7.3
94	4.9	7.4
95	5.4	8.2
7600	5.8	8.9
01	5.8	8.3
02	6.3	8.2
07	5.7	7.1
08	8.1	9.3
09	6.6	8.2
14	5.0	7.4
15	4.5	7.3
7660	5.1	7.2
61	5.6	7.4
62	4.1	6.5
63	3.8	6.8
64	2.9	3.7
65	4.1	6.8
66	3.2	3.6
67	4.5	2.2
Sub-Totals 1	Holes 22	112.0 154.7

Blast Hole	Pb	Zn
68	4.1	6.1
69	4.9	6.4
70	7.5	6.2
71	4.6	4.4
72	3.8	6.7
73	1.2	4.2
74		
75	4.2	5.8
76	3.3	5.8
77	5.9	5.0
78	6.0	6.6
79	4.5	6.2
80	3.3	6.3
81	4.5	5.8
82	6.1	6.1
83	3.9	5.9
84	5.6	3.5
85	3.0	4.9
86	2.1	5.4
87	4.7	4.7
7750	4.5	7.6
51	5.7	8.8
Sub-Totals 2	Holes 21	93.4 122.4

Blast Hole	Pb	Zn
52	5.2	7.5
53	5.5	7.8
54	5.6	8.0
55	5.0	7.3
56	3.3	6.1
57	2.5	5.8
58	1.8	6.8
59	4.3	7.9
60	3.6	8.9
61	5.0	8.5
62	4.5	7.6
63	5.5	8.8
64	3.3	6.9
65	6.0	8.7
66	3.9	7.7
67	4.0	8.0
68	5.0	9.5
69	4.7	9.5
70	4.9	7.5
71	3.0	8.4
72	2.1	8.2
Sub-Totals 3	Holes 21	88.7 165.4

Average Pb 4.4 Zn 7.0 Combined 11.4

Actual Tons Ore Mined _____

Remarks:

Page Total ---

Σ Pb 2	68	293.6	494.5
Σ Pb 3	68	283.6	479.0
Σ Pb 4	64	271.3	419.8
Σ Pb 5	53	244.4	370.5
	317	1387.0	2206.3

ORE BLOCK COMPARISON SHEET

3910

Dench

Date 31/2/71

D.D. Hole 66-16

Grade Pb Zn

Comb.

Tons

Blast Hole	Pb	Zn
7744	1.5	7.3
75	3.9	8.7
76	3.5	7.2
77	4.6	8.1
78	4.9	6.8
79	4.6	6.9
80	3.8	7.9
81	4.6	7.0
82	3.8	6.8
84	3.9	7.5
85	2.9	7.0
86	4.3	7.1
87	3.9	7.5
7797	1.8	6.2
98	4.0	6.8
99	4.4	7.0
7800	6.5	7.6
1	5.2	6.8
2	5.9	7.7
5	5.9	7.4
6	5.4	7.7
7	5.3	6.6
Sub-Totals	Holes 1 22	94.6 159.6

Blast Hole	Pb	Zn
8	5.0	7.4
9	3.5	7.7
10	1.7	6.1
11	2.4	6.6
12	2.4	6.1
13	2.6	7.1
14	4.2	6.2
15	4.8	6.2
16	5.8	7.6
17	3.6	6.1
78 67	3.3	7.3
68	3.7	7.6
69	3.7	8.0
70	4.3	7.2
77	4.7	6.6
78	3.6	6.5
98	4.1	7.9
7949	3.9	6.6
50	3.9	7.3
51	3.2	7.2
52	2.4	6.5
53	3.2	6.7
54	2.9	6.5
Sub-Totals	Holes 2 23	82.9 159.0

Blast Hole	Pb	Zn
8154	3.0	7.0
55	3.6	8.2
56	5.5	8.2
57	5.4	8.5
58	5.0	7.7
59	4.7	7.8
60	4.8	8.8
61	3.4	7.7
62	4.6	8.5
81 83	4.4	8.1
4	4.2	7.2
5	6.9	8.2
6	5.4	6.9
7	5.6	7.6
8	4.8	7.9
9	5.5	7.7
90	6.9	8.9
1	5.5	6.5
2	6.1	7.5
3	5.7	6.9
4	5.7	6.8
5	3.5	6.1
6	5.9	7.2
Sub-Totals	Holes 3 23	116.1 175.9
1	22	94.6 159.6
2	23	82.9 159.0
Page Total	68	293.6 494.5

Average Pb Zn Combined

Actual Tons Ore Mined

Page Total ---

Remarks:

D.D. Hole 66-16

Grade Pb Zn

Comb. Tons

Blast	Hole	Pb	Zn
	8199	5.5	6.9
	8200	4.0	8.9
	1	4.7	7.7
	2	4.7	6.6
	3	5.1	7.3
	4	5.5	7.9
	5	6.4	7.5
	6	5.8	6.9
	7	4.4	7.8
	8	3.8	7.8
	9	3.0	6.2
	10	1.7	5.0
	13	3.7	6.5
	14	5.4	7.8
	15	4.0	7.7
	16	4.5	7.9
	8219	3.0	7.6
	20	3.2	6.1
	21	4.5	7.2
	22	5.2	7.6
	23	4.5	7.3
	24	3.4	7.2
	27	3.4	7.7
Sub-Totals	23	99.4	167.1

Blast	Hole	Pb	Zn
	28	2.5	7.3
	29	2.5	6.9
	30	3.4	6.3
	31	5.3	7.5
	32	3.9	7.1
	33	2.7	6.8
	36	4.0	7.0
	37	4.1	7.1
	38		
	39	3.6	7.0
	40	3.7	7.2
	41	3.3	7.0
	42	4.7	7.9
	45	4.3	7.2
	46	3.8	7.8
	47	2.1	7.4
	48	1.8	6.4
	49	3.6	6.9
	50	3.2	6.3
	55	5.1	7.9
	56	3.6	6.9
	57	4.2	6.5
Sub-Totals	23	75.4	148.4

Blast	Hole	Pb	Zn
	58	4.0	7.1
	65	5.1	6.8
	8326	4.1	7.5
	35	6.4	7.7
	36	4.7	7.8
	37	5.5	7.2
	38	5.4	7.2
	39	5.3	6.8
	40	5.5	8.6
	41	5.0	7.3
	2	5.2	8.9
	3	5.5	9.2
	4	3.5	6.7
	5	5.4	7.2
	6	4.4	7.2
	7	5.2	7.7
	8	6.7	9.1
	49	5.8	7.4
	8443	4.1	6.5
	44	4.4	7.0
	45	3.4	6.1
	46	4.2	6.5
Sub-Totals	22	108.8	163.5
1	23	99.4	167.1
2	23	75.4	148.4
Page Total	68	283.6	479.0

Average Pb Zn Combined

Actual Tons Ore Mined

Remarks:

ORE BLOCK COMPARISON SHEET

3910

Bench

Date

D.D. Hole 66-16

Grade Pb

Zn

Comb.

Tons

Blast	Hole	Pb	Zn
	8447	3.9	5.9
	48	4.6	7.2
	49	4.4	7.2
	50	6.6	8.1
	51	5.6	7.7
	54	3.7	6.5
	55	4.3	7.3
	56	3.4	6.3
	57	4.9	8.3
	8493	5.4	6.8
	8505	4.1	6.8
	06	5.8	6.7
	07	3.6	7.7
	17	3.4	5.6
	18	2.0	4.1
	19	2.8	5.3
	26	4.2	7.1
	28	3.6	5.2
	8353	3.8	7.1
	54	5.3	7.7
	55	4.7	7.6
	56	2.9	4.8
Sub-Totals	1 Holes	22	93.0 147.0

Blast	Hole	Pb	Zn
	8357	3.4	6.4
	58	3.7	6.3
	59	4.3	6.3
	60	5.0	6.6
	61	4.2	5.8
	62	4.6	6.9
	63	3.2	4.2
	64	3.9	7.2
	65	5.3	7.1
	66	4.3	7.3
	67	3.5	5.8
	8368	2.9	6.1
	8534	5.5	6.8
	35	4.3	6.3
	36	4.2	6.3
	37	4.9	7.2
	38	4.8	6.6
	39	4.7	7.0
	41	3.5	6.4
	42	3.9	7.1
Sub-Totals	2 Holes	20	84.1 129.7

Blast	Hole	Pb	Zn
	43	4.0	6.9
	44	2.9	6.4
	45	4.4	6.8
	46	2.7	6.9
	8565	3.4	5.1
	66	3.2	8.3
	67	3.5	5.8
	68	4.0	8.0
	69	4.0	6.3
	70	4.7	7.0
	71	5.7	7.3
	72	3.7	5.8
	73	3.3	5.8
	74	4.7	6.9
	75	4.9	6.3
	76	5.1	6.5
	77	5.1	6.4
	78	2.1	4.0
	8583	4.9	7.0
	84	6.5	6.4
	85	5.6	6.5
	86	5.8	6.7
Sub-Totals	3 Holes	22	94.2 143.1
	1	22	93.0 147.0
	2	20	84.1 129.7
Page Total		64	271.3 419.8

Average Pb _____ Zn _____ Combined _____

Actual Tons Ore Mined _____

Remarks:

ORE BLOCK COMPARISON SHEET

3910

Bench

Date

D.D. Hole 66-16

Grade Fb Zn

Comb.

Tons

Blast	Hole	Pb	Zn
	8587	4.5	6.4
	89	5.5	6.6
	90	4.5	6.4
	91	2.3	2.9
	92	3.5	4.0
	93	4.6	5.9
	94	4.5	6.2
	95	5.2	6.4
	96	4.6	6.0
	97		
	98	4.2	7.0
	9802	3.9	5.1
	03	5.1	7.1
	4	4.2	6.4
	5	5.9	7.2
	6	5.5	7.4
	7	4.5	7.3
	8	5.8	7.4
	9	6.9	8.3
	10	4.9	7.2
	11	3.1	5.0
	12	4.4	6.1
	15	3.5	6.3
Sub-Totals	1	Holes 22	101.1 138.6

Blast	Hole	Pb	Zn
	8616	3.8	6.7
	17	4.3	6.7
	18	6.5	8.7
	19	6.3	8.8
	20	5.0	7.6
	8664	4.9	7.2
	65	4.6	8.1
	66	5.4	6.7
	67	3.4	7.0
	69	4.5	7.5
	70	4.5	8.8
	71	4.7	8.6
	73	2.7	7.2
	74	4.2	9.4
	93	5.8	7.2
	94	3.0	4.6
	95	2.0	4.2
	96	5.2	8.2
	97	5.5	7.9
	98	5.3	8.0
	99	5.5	7.4
Sub-Totals	2	Holes 21	97.1 156.5

Blast	Hole	Pb	Zn
	8700	6.3	9.6
	01	5.7	9.4
	02	5.5	9.0
	03	5.3	9.0
	04	4.4	8.3
	8711	2.7	7.1
	13	3.7	7.4
	15	4.6	6.4
	8752	6.1	5.8
	53	1.9	3.4
	5762		
	63		
Sub-Totals	3	Holes 10	46.2 75.4
	1	22	101.1 138.6
	2	21	97.1 156.5
Page Total		53	244.4 370.5

Average Pb Zn Combined

Actual Tons Ore Mined

Remarks: