

PREDICTED VS. MINED ORE GRADES & TONS. (1973)

ADJUSTED TO THOSE ORE BLOCKS ACTUALLY MINED & TO 74.5% Zn					BENCHES				
Predicted					Mined				
D.D.H.	TONS	Av % Pb	Av % Zn	Pb/Zn Ratio	D.D.H.	TONS	Av % Pb	Av % Zn	Pb/Zn Ratio
3910	546,961	3.34	6.37	.52	3910	597,370	3.74	4.76	.79
3870	945,760	3.73	5.64	.66	3870	1,132,551	4.48	5.67	.79
3830	1,324,632	4.85	6.21	.78	3830	1,422,739	4.75	6.03	.79
TOTAL	2,817,353	4.18	6.05	.69	TOTAL	3,152,660	4.47	5.66	.79
Difference	-335,307	-.29	+.39	-.10		+335,307	+.29	-.39	+.10

002110

PREDICTED VS. MINED ORE GRADES & TONS. (1973)

<small>ADJUSTED TO THOSE ORE BLOCKS ACTUALLY MINED @ TO 75% Zn</small> Predicted (3830 BENCH)					Mined (3830 BENCH)				
D.D.H.	TONS	Average Pb	Average Zn	Pb/Zn Ratio	D.D.H.	TONS	Average Pb	Average Zn	Pb/Zn Ratio
66-44	56,769	5.3	8.7(75)	.71	66-44	38,631	4.08	5.79	.70
66-32	55,591	2.4	5.0	.48	66-32	60,302	4.51	6.20	.73
65-11	113,773	7.3	8.9(75)	.97	65-11	129,083	5.09	7.23	.70
70-06	37,872	4.0	6.2	.65	70-06	97,520	4.98	6.08	.82
70-05	93,280	4.3	5.9	.73	70-05	93,279	3.80	5.70	.67
70-01	10,836	3.0	6.9	.43	70-01	12,248	3.30	5.32	.62
70-16	94,222	6.8	12.4(75)	.91	70-16	92,809	3.64	5.48	.66
65-04	27,325	4.0	6.1	.66	65-04	26,382	2.99	4.81	.62
70-02	78,205	1.8	3.6	.50	70-02	76,320	2.95	5.01	.59
70-03	11,307	3.2	7.9(75)	.43	70-03	10,364	2.98	5.10	.58
70-09	16,018	1.5	4.2	.36	70-09	17,902	4.41	5.17	.85
65-5A	188,444	4.9	5.7	.86	65-5A	177,127	5.25	6.31	.83
66-15	140,497	4.0	5.4	.74	66-15	183,968	4.61	5.60	.82
70-14	107,414	4.9	7.9(75)	.65	70-14	139,449	5.44	6.40	.85
66-12	3,109	3.1	5.6	.55	66-12	4,475	6.22	7.27	.86
66-23	57,947	6.4	6.8	.94	66-23	42,871	5.65	6.85	.82
65-08	15,076	6.3	9.2(75)	.84	65-08	7,538	5.89	7.64	.77
72-03	167,951	5.1	5.9	.86	72-03	160,178	5.65	6.26	.90
66-08	48,996	5.6	7.0	.80	66-08	52,293	5.76	5.63	1.02
TOTAL	1,324,632	4.85	6.21	.78	TOTAL	1,422,739	4.75	6.03	.79

PREDICTED VS. MINED ORE GRADES & TONS. (1973)

ADJUSTED TO THOSE ORE BLOCKS ACTUALLY MINED 70-25% Zn					Mined (3870 BENCH)				
Predicted (3870 BENCH)					Mined (3870 BENCH)				
D.D.H.	TONS	Av. % Pb	Av. % Zn	Pb/Zn Ratio	D.D.H.	TONS	Av. % Pb	Av. % Zn	Pb/Zn Ratio
70-01	53,707	2.9	6.6	.44	70-01	50,880	3.14	6.38	.49
65-04	63,129	6.0	6.7	.90	65-04	55,120	2.90	5.51	.53
70-16	9,894	2.7	6.5	.42	70-16	15,076	4.31	7.74	.56
70-03	55,591	4.6	9.2(75)	.50	70-03	50,409	3.65	6.06	.60
70-02	76,085	2.0	3.1	.65	70-02	58,418	3.38	5.23	.65
65-5A	63,129	6.0	6.7	.90	65-5A	44,284	5.39	5.92	.91
66-14	65,014	2.6	3.7	.70	66-14	73,493	3.42	4.16	.82
70-04	94,222	2.2	4.1	.54	70-04	81,973	3.81	4.90	.78
70-11	50,409	2.0	6.2	.32	70-11	48,996	3.37	4.84	.70
70-09 <small>70-09</small>	141,333	2.5	5.1	.49	70-09	139,920	5.81	5.83	.99
66-08	121,547	4.3	6.2	.69	66-08	135,209	4.71	5.15	.91
72-03	94,223	5.2	6.9	.75	72-03	273,244	4.94	6.15	.80
66-23	2,827	5.8	8.3(75)	.70	66-23	58,418	4.73	7.14	.66
66-04	3,769	1.8	3.9	.46	66-04	4,711	4.35	5.55	.78
72-07	50,881	6.2	6.3	.98	72-07	42,400	5.78	5.38	1.07
TOTAL	945,760	3.73	5.64	.66	TOTAL	1,132,551	4.48	5.67	.79

PREDICTED VS. MINED ORE GRADES & TONS. (1973)

ADJUSTED TO THOSE ORE
BLOCKS ACTUALLY MINED
70-75% Zn

Predicted (3910 BENCH)					Mined (3910 BENCH)				
D.D.H.	TONS	A _v % Pb	A _v % Zn	P _b /Z _n Ratio	D.D.H.	TONS	A _v % Pb	A _v % Zn	P _b /Z _n Ratio
70-03	80,089	3.7	6.8	.54	70-03	81,502	2.70	4.90	.55
70-02	-	-	-	-	70-02	1,884	-	-	-
70-08	9,422	1.8	4.1	.44	70-08	14,133	1.84	4.42	.42
66-14	88,569	3.4	7.4	.46	66-14	80,089	3.74	5.27	.71
66-39	13,191	3.6	8.7(75)	.41	66-39	32,978	2.85	5.46	.52
70-04	2,827	3.4	6.3	.54	70-04	2,827	5.90	6.50	.91
70-11	94,222	1.4	5.5	.25	70-11	92,338	3.98	5.04	.79
66-09	58,419	3.6	8.7(75)	.41	66-09	35,805	4.76	3.57	1.33
66-35	18,845	4.1	8.4(75)	.49	66-35	17,432	2.54	5.06	.50
66-04	15,075	1.8	3.9	.46	66-04	35,804	3.26	3.97	.82
70-09	73,493	4.2	6.0	.70	70-09	76,320	5.31	5.17	1.03
72-03	-	-	-	-	72-03	29,209 (GAIN)	2.93	4.52	.65
66-08	9,422	4.3	6.2	.69	66-08	9,422	3.30	4.12	.80
72-07	83,387	4.3	5.7	.75	72-07	87,627	4.08	4.26	.96
Total	546,961	3.34	6.37	.52	TOTAL	597,370	3.74	4.76	.79