

Jack

002715

Developed Ore for April, 1975 (as of April 01, 1975, using
Mar. 29, 75 Status Map)

Bench	Tonnage	% Pb	% Zn	Remarks
3750	58,158	4.5	5.7	all Broken
3790	206,677	4.4	6.7	North end
3830	206,438	3.4	4.3	excluding pyrite zones
<u>Total</u>	<u>471,273</u>	<u>4.0</u>	<u>5.5</u>	

Stockpiles; (unoxidized & dry)

C.F.S.P.#1	12,963	4.2	4.9	beside crusher
C.F.S.P.#2	41,276	3.3	4.5	opposite Crusher
<u>Total</u>	<u>54,239</u>	<u>3.5</u>	<u>4.6</u>	

Combined Dev. Ore & Stockpile Total:
525,512

3.95

5.24

R. J. Sambles

Apr. 8, 1975

Developed Ore for April, 1975 (Calc. from Apr. 1, 1975 using Mar. 29 status)

3750 Bench ('K' Blast only) - 58,158 Tons @ 4.5% Pb + 5.7% Zn
(12 PM, MAR, 31, '75)

3790 Bench (N. End)
(From Dev. Ore as of Feb. 20, '75) - 206,677 Tons @ 4.4% Pb + 6.7% Zn

3830 Bench (ORE) 206,438 Tons @ 3.4% Pb + 4.3% Zn
(There is an additional 12,485 Tons Pyrite in this area @ 1.5% Pb + 1.9% Zn)

Total Dev. Ore in Pit (excluding Py) 471,273 Tons @ 4.0% Pb + 5.5% Zn

CFSP#1 : 12,963 Tons @ 4.2% Pb + 4.9% Zn

CFSP#2 : 41,276 Tons @ 3.3% Pb + 4.5% Zn

CFSP Totals : 54,239 Tons @ 3.5% Pb + 4.6% Zn

Wet S.P. (frozen) : 45,720 Tons @ 5.1% Pb + 6.4% Zn