

002851

Ore Reserves
3990 Bench

<u>D.D.H.</u>	<u>Tonnage</u>	<u>Pb</u>	<u>Zn</u>	<u>Pb + Zn</u>
70-5	108,100	2.3	4.4	6.7
70-16	32,500	3.8	7.6	11.4
70-2	12,700	3.3	6.8	10.1
70-4	50,900	3.1	5.9	9.0
66-24	36,700	2.7	5.4	8.1
66-44	296,800	5.7	6.8	12.5
65-1	196,000	5.7	6.8	12.5
66-20	146,600	6.5	7.9	14.4
66-41	107,000	2.3	5.6	7.9
70-8	79,300	2.9	7.7	10.6
66-39	74,800	2.8	6.6	9.4
66-18	24,500	3.3	6.9	10.2
	<hr/>			
	1,165,900			

Ore Reserves
3050 Bench

<u>D.D.H.</u>	<u>Tonnage</u>	<u>Pb</u>	<u>Zn</u>	<u>Pb + Zn</u>
66-25	29,000	3.5	4.9	8.4
66-44	84,100	3.8	5.1	8.9
66-32	139,200	4.1	5.8	9.9
66-24	83,400	2.5	6.1	8.6
66-9	35,400	2.8	5.9	8.7
66-18	32,500	3.4 3.2	4.7 5.1	8.1 9.3
66-20	233,800	6.3	8.7	15.0
66-16	270,900	5.9	8.2	14.1
65-11	141,300	4.7	5.6	10.3
66-15	172,800	4.0	7.1	11.1
70-5	94,200	4.5	6.5	11.0
70-1	139,200	2.9	6.8	9.7
70-16	94,200	3.1	6.8	9.9
65-4	110,000	1.9	5.8	7.7
70-2	117,800	3.3	6.6	9.9
70-3	116,100	2.0	8.2	10.2
70-4	129,400	3.6	6.7	10.3
66-14	83,900	4.3	5.9	10.2
66-39	69,200	3.4	9.5	12.9
70-9	82,700	3.3	5.7	9.0
70-11	62,500	2.0	6.8	8.8
65-7	22,300	1.8	4.0	5.8
	<hr/>			
	2,343,900			

Ore Reserves
3910 Bench

<u>D.D.H.</u>	<u>Tonnage</u>	<u>Pb</u>	<u>Zn</u>	<u>Pb + Zn</u>
70-7	48,700	6.3	8.2	14.5
66-44	139,300	7.3	8.6	15.9
66-12	218,500	6.8	9.7	16.5
70-14	86,900	6.3	7.2	13.5
70-15	51,600	5.5	6.5	12.0
66-16	188,400	7.0	8.9	15.9
70-6	94,200	5.2	7.3	12.5
65-11	141,300	6.4	5.2	11.6
66-15	188,400	4.4	6.8	11.2
65-5A	183,600	4.7	5.8	10.5
66-32	112,600	4.0	7.8	11.8
70-5	94,200	3.0	7.8	10.8
70-16	94,200	2.4	5.5	7.9
70-2	94,200	2.0	4.0	6.0
70-4	94,200	3.4	6.3	9.7
70-9	99,500	4.2	6.0	10.2
70-1	183,000	3.0	5.7	8.7
65-4	107,700	5.3	8.8	14.1
70-3	101,400	3.7	6.8	10.5
66-14	107,400	3.4	7.4	10.8
65-7	132,700	2.6	7.2	9.8
66-35	115,000	4.1	8.4	12.5
66-9	73,900	3.6	8.7	12.3
	<u>2,750,900</u>			

Ore Reserves
3870 Bench

<u>D.D.H.</u>	<u>Tonnage</u>	<u>Pb</u>	<u>Zn</u>	<u>Pb + Zn</u>
66-44	106,000	8.0	10.7	18.7
65-11	235,700	6.7	7.4	14.1
66-32	96,100	3.6	3.9	7.5
66-12	188,600	3.1	5.5	8.6
70-6	137,400	4.8	7.9	12.7
66-15	188,400	5.5	6.4	11.9
70-5	94,200	3.2	6.6	9.8
70-1	124,900	2.9	6.6	9.5
70-16	82,400	2.9	7.3	10.2
65-4	105,500	3.7	6.2	9.9
66-23	88,900	5.6	9.1	14.7
70-7	60,000	5.0	8.2	13.2
70-2	47,100	3.0	4.5	7.5
70-3	126,400	4.6	9.1	13.7
70-14	106,500	5.2	8.6	13.8
65-5A	235,600	6.0	6.7	12.7
70-4	94,200	2.2	4.2	6.4
66-14	120,800	2.6	3.7	6.3
70-15	120,500	4.8	7.6	12.4
70-9	94,200	2.5	5.1	7.6
70-11	100,800	2.3	6.7	9.0
66-8	126,100	4.1	6.2	10.3
66-4	86,100	2.1	4.3	6.4
66-22	132,200	2.5	2.9	5.4
65-7	142,600	2.4	6.2	8.6
	<hr/>			
	3,041,200			

Ore Reserves
3830 Bench

<u>D.D.H.</u>	<u>Tonnage</u>	<u>Pb</u>	<u>Zn</u>	<u>Pb + Zn</u>
66-44	78,400	5.3	8.7	14.0
70-6	120,100	4.0	6.2	10.2
66-23	240,300	6.4	6.8	13.2
65-11	72,100	7.3	8.9	16.2
66-15	188,400	4.0	5.4	9.4
70-14	144,900	4.9	7.9	12.8
70-15	118,500	5.2	6.7	11.9
65-5A	235,600	4.9	5.6	10.5
66-8	357,600	5.5	7.0	12.5
66-35	130,000	1.9	6.5	8.4
70-5	94,200	4.3	5.9	10.2
70-16	94,200	6.8	12.4	19.2
70-2	94,200	1.8	3.6	5.4
70-9	47,300	2.3	6.6	8.9
70-1	61,700	3.0	6.9	9.9
65-4	86,400	4.0	6.1	10.1
70-3	90,600	3.2	7.9	11.1
66-14	128,300	6.4	10.8	17.2
70-11	71,000	3.0	5.1	8.1
66-9	83,800	2.7	5.7	8.4
66-4	212,000	2.3	4.6	6.9
66-32	18,600	3.3	5.7	9.0
66-22	405,600	3.5	5.4	8.9
65-7	135,100	2.6	7.4	10.0
UG-19	63,600	4.1	8.3	12.4
UG-21	36,700	5.2	8.3	13.5
	<u>3,409,200</u>			