

```
DDH: 65006      UTM-N:  9599.6      UTM-E:  14399.9      UTM-ELEV:  4099.8      TOTAL DEPTH:  500.0      SECTION:
RFE:           RFE DIR:  0 PLUNGE ANGLES:  0      0 DHD CALC:  1 SS CALC:  0
```

003481

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	ASSAYS													S.G. W.R.
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	
284.0	290.0	70004	5.0	.0	****	.50	.07	2.30	4.30	19.20										
290.0	295.0	70005	5.0	.0	****	.50		.40	5.40	30.20										
295.0	300.0	70006	5.0	.0	****	.50	.07	1.10	4.00	30.90										
300.0	305.0	70007	5.0	.0	****	.50	.15	1.50	4.20	30.20										
305.0	310.0	70008	5.0	.0	****	.50	.01	2.50	7.60	80.90										
310.0	315.0	70009	5.0	.0	****	.50		3.90	9.20	78.20										
315.0	320.0	70010	5.0	.0	****	.50	.07	2.10	4.10	12.30										
320.0	325.0	70011	5.0	.0	****	.50	.07	3.40	3.10	8.20										
325.0	330.0	70012	5.0	.0	****	.50	.16	1.70	1.60	8.20										
330.0	335.0	70013	5.0	.0	****	.50	.07	1.70	1.60	3.40										
335.0	340.0	70014	5.0	.0	****	.50			.70											
340.0	345.0	70015	5.0	.0	****	.50		.20	.20											
345.0	350.0	70016	5.0	.0	****	.50		3.90	3.20											
350.0	355.0	70017	5.0	.0	****	.50	.18	5.50	6.80	5.50										
355.0	360.0	70018	5.0	.0	****	.50	2.60	2.30	2.70	6.80										
360.0	365.0	70019	5.0	.0	****	.50		.70	2.50											
365.0	370.0	70020	5.0	.0	****	.50	.22	4.40	2.60	13.70										
370.0	375.0	70021	5.0	.0	****	.50		1.00	8.60	6.80										
375.0	380.0	70022	5.0	.0	****	.50	.27	1.60	4.40	12.30										
380.0	385.0	70023	5.0	.0	****	.50		.50	.70											
385.0	390.0	70024	5.0	.0	****	.50	.18	6.40	11.80	6.80										
390.0	395.0	70025	5.0	.0	****	.50	.37	1.60	3.60											
395.0	400.0	70026	5.0	.0	****	.50	.30	3.60	7.50											
400.0	405.0	70027	5.0	.0	****	.50		3.10	6.80											
405.0	410.0	70028	5.0	.0	****	.50	.07	4.70	9.60	8.20										
410.0	415.0	70029	5.0	.0	****	.50	.15	5.20	11.50	8.20										
415.0	420.0	70030	5.0	.0	****	.50		4.60	9.80	6.80										
420.0	425.0	70031	5.0	.0	****	.50		2.40	5.10	4.10										
425.0	430.0	70032	5.0	.0	****	.50		3.70	8.20	6.80										
430.0	435.0	70033	5.0	.0	****	.50		4.00	7.70	12.30										
435.0	440.0	70034	5.0	.0	****	.50		4.30	9.60	2.70										
440.0	445.0	70035	5.0	.0	****	.50		4.40	9.20	5.50										
445.0	450.0	70036	5.0	.0	****	.50		3.60	7.10	17.80										
450.0	455.0	70037	5.0	.0	****	.50		3.30	7.10	6.80										
455.0	460.0	70038	5.0	.0	****	.50		2.10	3.80											
460.0	465.0	70039	5.0	.0	****	.50		.40	1.10											
465.0	470.0	70040	5.0	.0	****	.50		2.80	6.20	5.50										
470.0	475.0	70041	5.0	.0	****	.50		3.00	7.50	13.70										
475.0	480.0	70042	5.0	.0	****	.50		2.90	5.20	30.20										
480.0	485.0	70043	5.0	.0	****	.50	.22	.70	1.70	12.30										


```
DDH: 65008      UTM-N: 9599.8      UTM-E: 13599.9      UTM-ELEV: 4169.1      TOTAL DEPTH: 600.0      SECTION:
RFE:          RFE DIR: 0 PLUNGE, ANGLES: 0      0 DHD CALC: 1      SS CALC: 0
```

[illegible]

DDH: 65009 UTM-N: 9199.8 UTM-E: 13998.3 UTM-ELEV: 4060.5 TOTAL DEPTH: 472.0 SECTION:
RFE: RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS----						-----ASSAYS-----																	
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.		
345.0	350.0	70114	5.0	.0	****	2.86	.24	.26	.57	6.00			5	5	11	.21		.12					
350.0	355.0	70115	5.0	.0	****	3.02	.24	.86	3.01	9.00			6	17	24	.13		.14					
355.0	360.0	70116	5.0	.0	****	3.25	.07	3.13	3.87	35.00			6	17	24	4.39		.14					
360.0	365.0	70117	5.0	.0	****	4.71	.19	5.00	6.52	70.00			6	17	24	16.14		.14					
365.0	370.0	70118	5.0	.0	****	4.44	.21	5.03	7.28	62.00			6	17	24	.17		.14					
370.0	375.0	70119	5.0	.0	****	4.15	.42	4.87	6.89	57.00			11	21	33	1.83		.16					
375.0	380.0	70120	5.0	.0	****	4.29	.45	3.04	5.44	46.00			11	21	33	8.32		.16					
380.0	385.0	70121	5.0	.0	****	4.54	.13	4.72	7.45	57.00			11	21	33	3.98		.16					
385.0	390.0	70122	5.0	.0	****	4.46	.09	5.18	6.82	49.00			11	21	33	.05		.16					
390.0	395.0	70123	5.0	.0	****	4.16	.12	3.72	5.92	30.00			11	25	37	.07		.12					
395.0	400.0	70124	5.0	.0	****	4.26	.13	5.63	5.02	58.00			11	25	37	.07		.12					
400.0	405.0	70125	5.0	.0	****	4.46	.57	5.50	7.81	54.00			11	25	37	.09		.12					
405.0	410.0	70126	5.0	.0	****	4.63	.25	5.30	7.21	44.00			11	25	37	.14		.12					
410.0	415.0	70127	5.0	.0	****	4.58	.21	6.01	7.28	47.00			7	25	32	.07		.14					
415.0	420.0	70128	5.0	.0	****	4.76	.23	4.71	5.21	47.00			7	25	32	9.08		.14					
420.0	425.0	70129	5.0	.0	****	4.53	.22	2.28	1.92	24.00			7	25	32	.07		.14					
425.0	430.0	70130	5.0	.0	****	3.67	.28	5.62	13.10	54.00			7	25	32	1.19		.14					
430.0	435.0	70131	5.0	.0	****	2.91	.09	1.46	4.13	26.00			3	2	6	.22		.05					
435.0	440.0	70132	5.0	.0	****	3.30	.06	17.60	2.51	82.00			3	2	6	.15		.05					
440.0	445.0	70133	5.0	.0	****	2.75	.06	1.33	2.68	23.00			3	2	6	.17		.05					
445.0	450.0	70134	5.0	.0	****	2.64	.05	1.38	2.76	24.00			3	2	6	.16		.05					
450.0	455.0	70135	5.0	.0	****	3.04	.09	3.92	3.67	67.00			6	6	12	.25		.06					
455.0	460.0	70136	5.0	.0	****	3.08	.09	9.11	5.68	139.00			6	6	12	.18		.06					
460.0	465.0	70137	5.0	.0	****	3.26	.36	1.53	4.51	36.00			6	6	12	.21		.06					
465.0	472.0	70138	7.0	.0	****	2.85	.13	1.37	3.33	29.00			6	6	12	.18		.06					

PAGE: 5

[illegible]

DDH: 66-03 UTM-N: 9200.0 UTM-E: 14398.0 UTM-ELEV: 4100.4 TOTAL DEPTH: 744.0 SECTION: 118+000
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	ASSAYS														
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
548.8	553.0	70219	4.2	.0	2C00	2.82	.10	.56	1.46	7.10				5	8	14	.31				.10
553.0	558.0	70220	5.0	.0	2D4	3.30	.14	2.49	8.93	31.50				5	8	14	.09				.10
558.0	563.0	70221	5.0	.0	2D4	3.33	.18	3.56	11.43	47.20				5	8	14	.10				.10
563.0	568.0	70222	5.0	.0	2F49	3.87	.32	4.38	8.13	71.60				5	8	14	.13				.10
568.0	573.0	70223	5.0	.0	2F49	4.88	.31	6.29	6.43	86.80				8	23	31	.08				.40
573.0	578.0	70224	5.0	.0	2F49	4.95	.27	7.30	7.46	98.90				8	23	31	.06				.40
578.0	583.0	70225	5.0	.0	2F46	4.95	.20	5.69	6.36	99.70				8	23	31	.29				.40
583.0	586.0	70226	3.0	.0	2F49	4.46	.34	7.17	7.14	89.70				8	23	31	.08				.40
586.0	590.6	70227	4.6	.0	2A00	2.95	.11	1.20	.92	32.80				8	23	31	2.44				.40
590.6	595.0	70228	4.4	.0	2A00	2.97	.12	1.90	1.80	30.80				4	4	8	3.02				.16
595.0	600.0	70229	5.0	.0	2B00	3.13	.07	1.72	1.68	30.90				4	4	8	4.83				.16
600.0	605.0	70230	5.0	.0	2D00	3.07	.07	1.24	1.96	13.20				4	4	8	3.29				.16
605.0	610.0	70231	5.0	.0	2B6	2.94	.02	.44	.86	7.00				4	4	8	4.32				.16
610.0	615.0	70232	5.0	.0	2D60	3.01	.05	.98	1.40	18.80				4	7	12	3.77				.10
615.0	620.0	70233	5.0	.0	2D60	2.90	.09	1.20	3.01	26.90				4	7	12	2.69				.10
620.0	624.0	70234	4.0	.0	2D0	3.05	.11	1.48	4.57	35.30				4	7	12	.33				.10
624.0	629.0	70235	5.0	.0	2D40	3.93	.22	9.45	9.51	152.00				4	7	12	.15				.10
629.0	634.0	70236	5.0	.0	2D40	4.15	.15	5.50	7.80	72.70							.12				
634.0	639.0	70237	5.0	.0	2C00	4.15	.07	.50	.70	4.10							.12				
639.0	644.0	70238	5.0	.0	2D90	4.15	.24	2.60	2.70	20.60							.12				
644.0	649.0	70239	5.0	.0	2D90	4.15	.19	3.60	4.80	20.60							.12				
649.0	654.0	70240	5.0	.0	2D90	4.80	.21	2.86	3.56	29.70				15	27	42	.09				.19
654.0	659.0	70241	5.0	.0	2E90	4.56	.29	2.30	.94	23.90				15	27	42	.04				.19
659.0	664.0	70242	5.0	.0	2A4&	4.29	.33	1.06	2.29	15.80				15	27	42	.03				.19
664.0	669.0	70243	5.0	.0	2A4&	3.23	.23	2.41	1.65	13.10				15	27	42	.05				.19
669.0	674.0	70244	5.0	.0	2E19	4.26	.32	1.68	1.42	23.80				10	31	41	.04				.12
674.0	679.0	70245	5.0	.0	2E19	4.57	.32	2.00	3.90	17.10				10	31	41	.02				.12
679.0	684.0	70246	5.0	.0	2A40	4.58	.16	3.42	4.18	67.30				10	31	41	.04				.12
684.0	689.0	70247	5.0	.0	2A40	4.26	.22	2.43	2.37	14.20				10	31	41	.06				.12
689.0	694.0	70248	5.0	.0	2A40	4.80	.11	3.30	4.81	17.40				3	16	19	.02				.06
694.0	699.0	70249	5.0	.0	2A40	3.32	.23	1.88	5.79	29.90				3	16	19	.09				.06
699.0	704.0	70250	5.0	.0	2A00	2.81	.07	1.36	2.54	30.40				3	16	19	.21				.06
704.0	709.0	70251	5.0	.0	2A40	2.93	.05	.90	3.51	30.20				3	16	19	.23				.06
709.0	714.0	70252	5.0	.0	2A40	2.78	.06	1.12	3.09	17.20				2	15	18	.22				.04
714.0	719.0	70253	5.0	.0	2A40	2.68	.09	1.14	4.63	54.80				2	15	18	.34				.04
719.0	724.0	70254	5.0	.0	2A40	4.25	.34	5.05	9.02	86.20				2	15	18	.06				.04
724.0	729.0	70255	5.0	.0	2A40	4.13	.13	2.56	5.79	29.60				2	15	18	.10				.04
729.0	734.0	70256	5.0	.0	2A40	3.01	.17	1.80	3.93	24.60				2	15	18	.21				.04
734.0	739.0	70257	5.0	.0	2A00	2.90		.20	1.30	6.20				2	15	18	.20				.04

DDH: 66-05 UTM-N: 8800.1 UTM-E: 13999.5 UTM-ELEV: 4018.1 TOTAL DEPTH: 673.2 SECTION: 113+000
RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %
489.0	494.0	70320	5.0	.0	2A0	3.04	.06	.34	.96	9.20			3	7	10	.11		.07		
494.0	499.0	70321	5.0	.0	2A0	3.20	.10	.40	.92	10.80			3	7	10	.13		.07		
499.0	504.0	70322	5.0	.0	2A0	3.04	.08	1.36	1.77	18.20			3	7	10	.07		.07		
504.0	509.0	70323	5.0	.0	2A0	2.52	.03	.88	2.86	13.20			3	7	10	.32		.07		
509.0	514.0	70324	5.0	.0	2A4	3.09	.05	1.28	4.00	22.10			4	11	16	.19		.06		
514.0	519.0	70325	5.0	.0	2F40	4.07	.09	5.21	9.11	65.20			4	11	16	.09		.06		
519.0	524.0	70326	5.0	.0	2C00	2.86	.16	1.68	2.20	33.40			4	11	16	.34		.06		
524.0	529.0	70327	5.0	.0	2C00	3.17	.18	.96	1.98	31.10			4	11	16	.38		.06		
529.0	534.0	70328	5.0	.0	2D0	3.43	.14	2.79	7.00	50.20			4	8	13	.16		.04		
534.0	539.0	70329	5.0	.0	2E40	3.21	.21	1.94	3.93	35.30			4	8	13	.16		.04		
539.0	544.0	70330	5.0	.0	2A0	2.82	.10	.74	2.03	14.20			4	8	13	.19		.04		
544.0	549.0	70331	5.0	.0	2A0	2.88	.04	1.10	1.82	29.30			4	8	13	.20		.04		
549.0	554.0	70332	5.0	.0	2A0	2.60	.14	2.08	1.36	29.30			4	8	13	.20		.04		

DDH: 66-06 UTM-N: 9599.5 UTM-E: 14800.0 UTM-ELEV: 4188.3 TOTAL DEPTH: 766.0 SECTION: 118+000
 RFE: 82 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	ASSAYS													
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %
423.5	428.3	70337	4.8	.0	2D34	3.96	.16	2.80	7.90	109.70			3	17	20	.20		.06		
437.0	441.0	70339	4.0	.0	2H11	3.14	.01	2.50	2.60	69.90			12	18	30	.20		.09		
456.0	460.0	70341	4.0	.0	2E00	3.10	.16	.93	3.15	20.40			4	22	26	.18		.07		
460.0	465.0	70342	5.0	.0	2D46	3.28	.19	2.89	9.07	40.10			4	22	26	.20		.07		
465.0	470.0	70343	5.0	.0	2E40	4.60	.28	2.84	4.91	52.60			4	22	26	.06		.07		
470.0	475.0	70344	5.0	.0	2E00	4.56	.19	.35	1.36	8.70			4	22	26	.07		.07		
475.0	480.0	70345	5.0	.0	2D40	4.00	.27	3.29	6.91	29.80			4	22	26	.10		.07		
480.0	485.0	70346	5.0	.0	2D00	3.71	.06	1.35	3.38	15.60			3	26	30	.12		.09		
485.0	490.0	70347	5.0	.0	2E10	3.59	.04	1.00	2.80	14.60			3	26	30	.09		.09		
490.0	495.0	70348	5.0	.0	2E81	4.04	.29	.30	.84	19.10			3	26	30	.04		.09		
495.0	500.0	70349	5.0	.0	2E81	3.89	.29		.86	7.10			3	26	30	.03		.09		
500.0	505.0	70350	5.0	.0	2E81	4.06	.31	.69	1.66	9.30			3	26	30	.03		.15		
505.0	510.0	70351	5.0	.0	2E81	4.10	.22	.51	1.04	6.60			3	26	30	.02		.15		
510.0	515.0	70352	5.0	.0	2E81	3.93	.23	.93	1.92	13.70			3	26	30	.05		.15		
515.0	520.0	70353	5.0	.0	2A40	3.81	.09	3.53	7.29	146.00			3	26	30	.10		.15		
520.0	524.0	70354	4.0	.0	2A40	3.22	.14	3.26	4.60	55.20			4	17	21	.17		.11		
524.0	529.0	70355	5.0	.0	2C3	3.32	.23	1.89	1.64	40.50			4	17	21	.11		.11		
529.0	534.0	70356	5.0	.0	2D00	3.69	.16	2.90	2.35	46.70			4	17	21	.10		.11		
534.0	539.0	70357	5.0	.0	2C30	3.74	.14	.56	1.56	14.00			4	17	21	.08		.11		
539.0	544.0	70358	5.0	.0	2C3	3.88	.12	.55	1.80	11.50			2	27	29	.05		.06		
544.0	549.0	70359	5.0	.0	2C30	4.57	.07	.10	1.74	3.90			2	27	29	.04		.06		
549.0	554.0	70360	5.0	.0	2D3	4.17	.10	1.63	4.58	11.30			2	27	29	.05		.06		
554.0	559.0	70361	5.0	.0	2D3	4.29	.25	2.22	2.84	22.00			2	27	29	.03		.06		
559.0	564.0	70362	5.0	.0	2D46	3.71	.07	4.43	7.87	16.00			2	21	24	.06		.03		
564.0	569.0	70363	5.0	.0	2D3	3.94	.08	1.82	5.80	12.10			2	21	24	.06		.03		
569.0	574.0	70364	5.0	.0	2D45	3.55	.10	3.10	11.22	12.50			2	21	24	.14		.03		
574.0	579.0	70365	5.0	.0	2D43	4.07	.05	4.82	9.17	16.10			2	21	24	.05		.03		
579.0	584.0	70366	5.0	.0	2D46	3.75	.07	4.65	10.19	16.50			3	23	26	.06		.05		
584.0	589.0	70367	5.0	.0	2D46	3.62	.04	5.66	11.10	12.70			3	23	26	.09		.05		
589.0	594.0	70368	5.0	.0	2E41	4.00	.04	2.06	6.18	7.60			3	23	26	.06		.05		
594.0	599.0	70369	5.0	.0	2E41	4.25	.06	2.14	4.90	8.20			3	23	26	.03		.05		
599.0	604.0	70370	5.0	.0	2D43	3.70	.05	3.74	9.66	21.70			3	17	21	.10		.04		
604.0	609.0	70371	5.0	.0	2D43	3.44	.06	2.00	7.14	16.00			3	17	21	.17		.04		
609.0	614.0	70372	5.0	.0	2E48	4.22	.04	1.76	5.56	20.30			3	17	21	.08		.04		
614.0	619.0	70373	5.0	.0	2D00	3.13	.18	2.69	5.95	73.70			3	17	21	.27		.04		
619.0	622.8	70374	3.8	.0	2D00	3.07	.07	1.33	4.01	22.60			3	17	21	.32		.04		

DDH: 66-07 UTM-N: 9200.6 UTM-E: 14798.3 UTM-ELEV: 4156.7 TOTAL DEPTH: 810.0 SECTION: 120+000
RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	ASSAYS													
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %
588.0	593.0	70382	5.0	.0	2E48	4.18	.07	5.35	6.20	54.30			7	22	30	.16		.13		
593.0	598.0	70383	5.0	.0	2E48	4.16	.09	2.88	3.87	26.00			7	22	30	.10		.13		
598.0	603.0	70384	5.0	.0	2E30	3.93	.07	1.78	2.30	19.50			7	22	30	.08		.13		
603.0	608.0	70385	5.0	.0	2D40	3.60	.17	3.26	5.90	15.10			7	22	30	.07		.13		
608.0	613.0	70386	5.0	.0	2D49	3.97	.21	3.84	9.76	13.80			4	25	30	.05		.16		
613.0	618.0	70387	5.0	.0	2E89	4.32	.25	1.18	2.84	7.80			4	25	30	.02		.16		
618.0	623.0	70388	5.0	.0	2D4	4.84	.13	4.13	8.36	10.00			4	25	30	.02		.16		
623.0	628.0	70389	5.0	.0	2F41	4.39	.06	4.51	12.51	13.60			4	25	30	.05		.16		
628.0	633.0	70390	5.0	.0	2D40	3.39	.02	3.97	8.36	20.00			4	20	24	.06		.04		
633.0	638.0	70391	5.0	.0	2D40	4.01	.02	2.78	6.58	14.00			4	20	24	.09		.04		
638.0	643.0	70392	5.0	.0	2E40	4.55	.16	8.34	19.56	47.00			4	20	24	.06		.04		
643.0	648.0	70393	5.0	.0	2F40	3.67	.06	3.78	10.87	27.40			4	20	24	.17		.04		
648.0	658.0	70394	10.0	.0	2C0	3.03	.06	.96	2.24	19.20			3	13	17	.27		.03		
658.0	663.0	70395	5.0	.0	2C0	3.20	.16	.35	2.36	9.50			3	13	17	.20		.03		
663.0	668.0	70396	5.0	.0	2A30	3.24	.04	.25	1.66	18.50			3	13	17	.17		.03		
668.0	673.0	70397	5.0	.0	2A30	3.40	.04	1.06	1.46	29.00			3	13	17	.23		.04		
673.0	678.0	70398	5.0	.0	2D00	2.95	.12	1.76	4.33	22.70			3	13	17	.22		.04		

DDH: 66-10 UTM-N: 8790.5 UTM-E: 14795.4 UTM-ELEV: 4121.4 TOTAL DEPTH: 849.0 SECTION: 122+020
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	ASSAYS													
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Pt %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %
570.0	575.0	70470	5.0	.0	2D49	4.03	.26	4.56	6.10	79.20			10	8	19	1.77		.18		
575.0	580.0	70471	5.0	.0	2E43	3.33	.17	4.25	4.65	94.00			10	8	19	4.47		.18		
580.0	585.0	70472	5.0	.0	2C30	2.82	.05	.50	.48	15.70			10	8	19	1.21		.18		
585.0	590.0	70473	5.0	.0	2K0*	2.76	.10	.40	.24	10.80			10	8	19	2.42		.18		
590.0	595.0	70474	5.0	.0	2E13	3.91	.46	2.00	1.24	41.50			5	32	37	.20		.12		
595.0	600.0	70475	5.0	.0	2E40	4.66	.10	4.56	4.08	53.30			5	32	37	.05		.12		
600.0	605.0	70476	5.0	.0	2E08	3.95	.07	1.64	1.10	22.10			5	32	37	.06		.12		
605.0	610.0	70477	5.0	.0	2E98	4.57	.20	1.60	.78	22.90			5	32	37	.05		.12		
610.0	615.0	70478	5.0	.0	2E98	4.94	.21	1.20	.46	26.40			2	36	39	.09		.05		
615.0	620.0	70479	5.0	.0	2E08	4.60	.11	1.30	.46	18.40			2	36	39	.04		.05		
620.0	625.0	70480	5.0	.0	2E08	3.80	.18	1.22	.82	63.80			2	36	39	.89		.05		
625.0	630.0	70481	5.0	.0	2E08	4.34	.19	1.14	.64	21.80			2	36	39	.05		.05		
630.0	634.0	70482	4.0	.0	2E08	4.73	.15	.94	1.16	17.10			3	35	39	.88		.08		
634.0	638.0	70483	4.0	.0	2E08	4.17	.15	1.52	1.83	21.70			3	35	39	1.23		.08		
638.0	639.0	70484	1.0	.0	2E08	.50	.15	1.52	1.83	21.70			3	35	39	1.23		.08		
639.0	644.0	70485	5.0	.0	2E19	5.05	.23	2.91	4.57	29.40			2	31	33	2.48		.10		
644.0	649.0	70486	5.0	.0	2G4	4.64		2.75	5.98	27.60			2	31	33	24.07		.10		
649.0	654.0	70487	5.0	.0	2G40	4.69	.14	2.67	4.01	30.00			2	31	33	5.95		.10		
654.0	659.0	70488	5.0	.0	2E08	4.60	.12	2.03	2.23	21.70			2	33	36	2.29		.10		
659.0	664.0	70489	5.0	.0	2E00	3.90	.06	.40	.22	5.30			2	33	36	.13		.10		
664.0	669.0	70490	5.0	.0	2E00	4.21	.12	.94	.67	15.80			2	33	36	.06		.10		
669.0	674.0	70491	5.0	.0	2E49	4.52	.26	3.44	3.55	50.00			2	33	36	.07		.10		
674.0	679.0	70492	5.0	.0	2E41	4.64	.30	3.58	3.16	41.10			3	34	37	.12		.10		
679.0	684.0	70493	5.0	.0	2E49	4.88	.29	3.61	2.92	45.00			3	34	37	.09		.10		
684.0	689.0	70494	5.0	.0	2E08	4.93	.17	2.11	1.29	26.30			3	34	37	.63		.10		
689.0	694.0	70495	5.0	.0	2G0	4.41	.16	3.06	4.61	83.30			3	34	37	15.63		.10		
694.0	699.0	70496	5.0	.0	2E49	4.57	.25	2.37	3.26	30.90			5	33	39	1.50		.18		
699.0	704.0	70497	5.0	.0	2E49	4.47	.21	2.42	3.78	29.20			5	33	39	.09		.18		
704.0	709.0	70498	5.0	.0	2E19	4.31	.24	1.30	2.55	16.00			5	33	39	.08		.18		
709.0	714.0	70499	5.0	.0	2E19	4.60	.24	2.65	4.65	23.80			5	33	39	.09		.18		
714.0	719.0	70500	5.0	.0	2E48	4.51	.18	3.04	4.63	18.80			5	31	36	.44		.14		
719.0	724.0	70501	5.0	.0	2E40	4.61	.15	2.81	5.14	12.20			5	31	36	.02		.14		
724.0	729.0	70502	5.0	.0	2E40	4.88	.10	4.05	7.86	17.80			5	31	36	.02		.14		
729.0	734.0	70503	5.0	.0	2C90	4.30	.20	2.96	7.26	13.70			5	31	36	.05		.14		
734.0	739.0	70504	5.0	.0	2A00	2.48	.17	.65	1.82	11.60			3	3	6	.24		.04		
739.0	744.0	70505	5.0	.0	2A00	2.65	.11	.80	1.84	13.20			3	3	6	.37		.04		
744.0	749.0	70506	5.0	.0	2B0	2.73	.04	1.13	2.36	14.20			3	3	6	.35		.04		
749.0	754.0	70507	5.0	.0	2B40	2.89	.03	1.37	4.42	15.60			3	3	6	.31		.04		
754.0	759.0	70508	5.0	.0	2B0	2.84	.07	.75	2.83	9.60			4	12	16	.42		.04		
759.0	764.0	70509	5.0	.0	2D37	3.23	.24	.74	3.64	13.30			4	12	16	.16		.04		
764.0	769.0	70510	5.0	.0	2D37	3.43	.35	1.35	4.73	18.30			4	12	16	.10		.04		
769.0	774.0	70511	5.0	.0	2A10	2.90	.22	.33	1.84	9.40			4	12	16	.28		.04		
774.0	779.0	70512	5.0	.0	2A1	2.63	.03	.98	1.17	5.40			4	12	16	.31		.04		

DDH: 66-11 UTM-N: 9199.3 UTM-E: 15199.7 UTM-ELEV: 4191.5 TOTAL DEPTH: 759.5 SECTION: 122+020
RFE: 92 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

-----DEPTHS----						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
551.0	556.0	70521	5.0	.0	2C39	3.36	.17	.94	1.43	19.30			6	13	20	.10		.06			
556.0	561.0	70522	5.0	.0	2C35	3.09	.17	1.11	2.23	23.30			6	13	20	.16		.06			
561.0	566.0	70523	5.0	.0	2D35	3.25	.05	2.19	4.35	26.80			4	13	18	.15		.04			
566.0	571.0	70524	5.0	.0	2C50	3.12	.16	.79	2.06	16.40			4	13	18	.21		.04			
571.0	576.0	70525	5.0	.0	2C50	3.37	.05	1.07	1.62	21.30			4	13	18	.16		.04			
576.0	581.0	70526	5.0	.0	0Q90	2.94	.10	1.16	3.28	18.90			4	13	18	.12		.04			
581.0	586.0	70527	5.0	.0	2C00	3.08	.06	1.12	1.93	18.80			5	7	12	.24		.02			
586.0	591.0	70528	5.0	.0	2C00	2.87	.14	.68	2.07	33.10			5	7	12	.34		.02			
591.0	596.0	70529	5.0	.0	2C90	2.94	.26	5.53	1.27	202.90			5	7	12	.22		.02			
596.0	601.0	70530	5.0	.0	2C00	3.01	.13	1.63	2.68	37.20			5	7	12	.25		.02			

DDH: 66-46 UTM-N: 9398.9 UTM-E: 14599.9 UTM-ELEV: 4161.1 TOTAL DEPTH: 800.0 SECTION: 118+000
 RFE: 92 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	ASSAYS													
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Pt %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %
480.0	485.0	70804	5.0	.0	10E90	2.96	.13	3.01	2.95	26.50			13	7	20	3.59		.24		
485.0	490.0	70805	5.0	.0	2D47	4.03	.19	4.38	5.65	67.70			13	7	20	9.16		.24		
490.0	495.0	70806	5.0	.0	2J84	3.94	.10	6.03	6.57	29.90			14	18	33	5.67		.35		
495.0	500.0	70807	5.0	.0	2E4*	3.86	.15	2.33	3.04	31.90			14	18	33	2.16		.35		
500.0	505.0	70808	5.0	.0	2E89	3.83	.22	1.82	1.69	28.50			14	18	33	.93		.35		
505.0	510.0	70809	5.0	.0	2G42	4.30	.30	5.32	4.76	56.40			14	18	33	3.59		.35		
510.0	515.0	70810	5.0	.0	2J89	3.85	.47	2.83	3.16	51.60			17	9	26	7.87		.35		
515.0	520.0	70811	5.0	.0	2J8*	4.20	.10	3.41	3.16	36.00			17	9	26	6.78		.35		
520.0	525.0	70812	5.0	.0	2G4	4.44	.13	6.85	6.76	90.30			17	9	26	23.70		.35		
525.0	530.0	70813	5.0	.0	2G4&	4.61	.14	5.76	6.33	75.50			17	9	26	23.07		.35		
530.0	535.0	70814	5.0	.0	2G4&	4.68	.11	8.10	7.30	103.40			4	21	25	26.06		.29		
535.0	540.0	70815	5.0	.0	2G4&	4.49	.10	5.68	6.28	77.20			4	21	25	23.15		.29		
540.0	545.0	70816	5.0	.0	2G4&	4.75	.13	4.38	5.14	59.40			4	21	25	17.72		.29		
545.0	550.0	70817	5.0	.0	2G4&	4.48	.13	3.20	4.63	41.90			4	21	25	7.91		.29		
550.0	555.0	70818	5.0	.0	2E48	3.29	.16	2.41	3.25	37.00			2	27	30	.18		.11		
555.0	560.0	70819	5.0	.0	2C3	3.28	.06	1.77	.19	69.10			2	27	30	.04		.11		
560.0	565.0	70820	5.0	.0	2C3	3.51	.02	.18	.14	11.90			2	27	30	.04		.11		
565.0	570.0	70821	5.0	.0	2E41	4.54	.12	2.50	1.83	27.70			2	27	30	.02		.11		
570.0	575.0	70822	5.0	.0	2E41	4.66	.10	2.33	1.91	25.80			4	36	40	.03		.12		
575.0	580.0	70823	5.0	.0	2E41	4.23	.33	1.36	2.61	17.90			4	36	40	.08		.12		
580.0	585.0	70824	5.0	.0	2E84	4.45	.21	2.37	2.95	20.70			4	36	40	.09		.12		
585.0	590.0	70825	5.0	.0	2E08	4.69	.20	.52	.67	2.70			4	36	40	.02		.12		
590.0	595.0	70826	5.0	.0	2E08	4.59	.18	1.16	2.33	4.20			5	31	36	.03		.13		
595.0	600.0	70827	5.0	.0	2E48	4.61	.14	4.06	8.82	13.90			5	31	36	.02		.13		
600.0	605.0	70828	5.0	.0	2E48	4.27	.44	2.11	2.75	20.60			5	31	36	.04		.13		
605.0	610.0	70829	5.0	.0	2F0	5.12	.11	2.65	6.52	5.80			5	31	36	.06		.13		
610.0	615.0	70830	5.0	.0	2F4	5.06	.08	3.45	6.99	9.40			3	35	38	.34		.04		
615.0	620.0	70831	5.0	.0	2F4	5.02	.07	4.88	7.65	18.10			3	35	38	.16		.04		
620.0	625.0	70832	5.0	.0	2F4	4.73	.05	5.35	9.58	16.80			3	35	38	.27		.04		
625.0	630.0	70833	5.0	.0	2E48	4.75	.20	1.13	4.85	2.50			3	35	38	.03		.04		
630.0	635.0	70834	5.0	.0	2E48	4.52	.23	1.82	3.44	4.90			7	32	39	.03		.17		
635.0	640.0	70835	5.0	.0	2E48	4.52	.24	2.44	4.31	7.80			7	32	39	.02		.17		
640.0	645.0	70836	5.0	.0	2E81	4.08	.26	.97	2.30	2.00			7	32	39	.02		.17		
645.0	650.0	70837	5.0	.0	2E81	4.09	.56	.64	2.23	4.10			7	32	39	.02		.17		
650.0	655.0	70838	5.0	.0	2E81	4.56	.43	2.38	4.82	8.20			10	25	36	.02		.07		
655.0	660.0	70839	5.0	.0	2F4	4.85	.07	4.95	9.64	11.10			10	25	36	.02		.07		
660.0	665.0	70840	5.0	.0	2F40	3.92	.08	3.61	6.30	17.80			10	25	36	.08		.07		
665.0	670.0	70841	5.0	.0	2H48	4.05	.28	6.27	14.31	44.50			10	25	36	.06		.07		
670.0	675.0	70842	5.0	.0	2H48	3.11	.23	1.72	5.47	31.20			6	15	21	.14		.02		
675.0	680.0	70843	5.0	.0	2C7&	3.02	.15	.56	.26	8.60			6	15	21	.09		.02		
680.0	685.0	70844	5.0	.0	2A1	3.02	.03	.85	1.76	10.30			6	15	21	.10		.02		
685.0	690.0	70845	5.0	.0	2D4&	3.79	.04	3.88	12.15	28.50			6	15	21	.05		.02		
690.0	695.0	70846	5.0	.0	2D4&	4.01	.05	1.83	5.32	21.00			1	35	37	.04		.02		
695.0	700.0	70847	5.0	.0	2E44	5.08	.02	3.15	4.34	14.40			1	35	37	.01		.02		
700.0	705.0	70848	5.0	.0	2E44	4.50	.05	4.09	8.42	19.30			1	35	37	.02		.02		
705.0	710.0	70849	5.0	.0	2E4	5.20	.02	3.51	3.07	16.40			1	35	37	.01		.02		
710.0	715.0	70850	5.0	.0	2F1	3.44	.02	3.51	4.42	15.80			2	30	33	.01		.02		
715.0	720.0	70851	5.0	.0	2F1	3.65	.03	2.72	5.19	14.80			2	30	33	.02		.02		
720.0	725.0	70852	5.0	.0	2F1	3.59	.10	2.62	6.88	19.80			2	30	33	.11		.02		
725.0	730.0	70853	5.0	.0	2D4&	3.65	.09	4.12	10.21	29.00			2	30	33	.06		.02		
730.0	735.0	70854	5.0	.0	2D4&	3.42	.17	5.96	10.96	115.50			7	9	16	.05		.03		

DDH: 66-46 UTM-N: 9398.9 UTM-E: 14599.9 UTM-ELEV: 4161.1 TOTAL DEPTH: 800.0 SECTION: 118+000
RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

-----DEPTHS----						-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
735.0	740.0	70855	5.0	.0	2D48	2.92	.27	2.87	7.41	40.50		7	9	16	.16		.03			
740.0	745.0	70856	5.0	.0	2A97	3.18	.19	.84	2.52	20.80		7	9	16	.22		.03			
745.0	750.0	70857	5.0	.0	2C79	3.03	.22	.25	1.55	13.80		7	9	16	.33		.03			
750.0	755.0	70858	5.0	.0	2C79	2.99	.35	.04	.31	21.20		15	1	16	.29		.02			
755.0	760.0	70859	5.0	.0	2C79	2.97	.27	.60	1.27	23.10		15	1	16	.20		.02			

DDH: 66-47 UTM-N: 9599.8 UTM-E: 15199.8 UTM-ELEV: 4217.1 TOTAL DEPTH: 700.0 SECTION: 120+000
RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

---DEPTHS---		SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														
FROM	TO					Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Pt %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
590.0	595.0	70867	5.0	.0	2L40	2.90	.19	1.41	.10	219.90			3	4	7	.12		.05		
595.0	600.0	70868	5.0	.0	2L40	2.73	.09	.56	.09	49.00			3	4	7	.14		.05		
600.0	605.0	70869	5.0	.0	2L40	2.78	.02	.04	.09	1.20			3	4	7	.16		.05		
605.0	610.0	70870	5.0	.0	2D00	3.07	.12	1.75	3.53	14.40			3	4	7	.12		.05		
610.0	615.0	70871	5.0	.0	2D00	3.16	.31	2.50	4.41	32.20			5	7	12	.14		.04		
615.0	620.0	70872	5.0	.0	2B9A	3.00	.20	.96	1.57	27.00			5	7	12	.22		.04		

DDH: 66-49 UTM-N: 8799.3 UTM-E: 14399.5 UTM-ELEV: 4059.5 TOTAL DEPTH: 750.0 SECTION: 120+000
RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %
555.0	560.0	70877	5.0	.0	2H43	3.22	.16	2.56	3.21	41.00			15	13	29	.19		.25		
560.0	565.0	70878	5.0	.0	2H43	4.87	.23	6.00	7.66	78.40			15	13	29	.17		.25		
565.0	570.0	70879	5.0	.0	2H49	4.47	.29	8.79	9.53	117.70			15	13	29	.10		.25		
570.0	575.0	70880	5.0	.0	2H49	4.71	.42	7.48	8.09	98.80			12	14	26	1.14		.36		
575.0	580.0	70881	5.0	.0	2D47	3.73	.18	3.84	4.04	59.10			12	14	26	1.84		.36		
580.0	585.0	70882	5.0	.0	2L14	3.05	.14	2.73	2.83	42.20			12	14	26	3.09		.36		
585.0	590.0	70883	5.0	.0	2H49	4.53	.27	7.08	9.26	100.30			12	14	26	.62		.36		
590.0	595.0	70884	5.0	.0	2G49	4.68	.20	4.57	6.88	41.80			5	20	25	7.31		.13		
595.0	600.0	70885	5.0	.0	2E11	5.07	.17	1.31	1.94	17.30			5	20	25	.34		.13		
600.0	605.0	70886	5.0	.0	2B49	2.76	.22	2.07	3.58	46.70			5	20	25	.26		.13		
605.0	610.0	70887	5.0	.0	2B49	2.99	.23	3.69	2.01	67.60			5	20	25	.31		.13		
610.0	615.0	70888	5.0	.0	2B0	2.76	.09	.72	1.97	15.10			9	20	30	.41		.10		
615.0	620.0	70889	5.0	.0	2B49	3.40	.30	2.14	3.50	37.90			9	20	30	.38		.10		
620.0	625.0	70890	5.0	.0	2E91	4.84	.47	1.40	1.31	21.90			9	20	30	.02		.10		
625.0	630.0	70891	5.0	.0	2E91	5.15	.42	2.82	1.16	21.60			9	20	30	.02		.10		
630.0	635.0	70892	5.0	.0	2E91	4.77	.42	3.93	3.77	26.50			5	34	40	.02		.17		
635.0	640.0	70893	5.0	.0	2E91	4.46	.24	2.64	5.06	20.60			5	34	40	.03		.17		
640.0	645.0	70894	5.0	.0	2F49	4.71	.46	5.28	4.63	35.90			5	34	40	.02		.17		
645.0	650.0	70895	5.0	.0	2F4	4.93	.12	4.30	7.12	24.60			5	34	40	.02		.17		
650.0	655.0	70896	5.0	.0	2A49	3.54	.24	2.24	4.61	21.10			5	10	16	.18		.05		
655.0	660.0	70897	5.0	.0	2A4	2.72	.05	1.09	3.23	23.70			5	10	16	.32		.05		
660.0	665.0	70898	5.0	.0	2A4	2.92	.08	1.25	3.13	34.80			5	10	16	.23		.05		
665.0	670.0	70899	5.0	.0	2D91	3.49	.28	2.03	4.72	51.10			5	10	16	.17		.05		
670.0	675.0	70900	5.0	.0	2D01	3.27	.19	1.57	3.11	32.10			5	5	11	.28		.08		
675.0	680.0	70901	5.0	.0	2A41	3.02	.10	2.47	2.51	53.40			5	5	11	.15		.08		
680.0	685.0	70902	5.0	.0	2A4	2.88	.10	1.26	3.19	29.20			5	5	11	.16		.08		

DDH: 66-52 UTM-M: 8996.9 UTM-E: 14199.1 UTM-ELEV: 4038.8 TOTAL DEPTH: 725.0 SECTION: 118+000
 RFE: 52 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
515.0	520.0	70907	5.0	.0	2H49	4.48	.38	5.17	7.34	58.00			20	6	27	.19		.11			
520.0	525.0	70908	5.0	.0	2D49	4.05	.38	6.34	9.32	69.80			20	6	27	.17		.11			
525.0	530.0	70909	5.0	.0	2D0	2.59	.09	2.27	6.05	31.10			20	6	27	.15		.11			
530.0	535.0	70910	5.0	.0	2D40	3.93	.21	5.31	8.11	71.60			8	25	33	.17		.11			
535.0	540.0	70911	5.0	.0	2F4	4.67	.20	5.68	7.85	56.00			8	25	33	.10		.11			
540.0	545.0	70912	5.0	.0	2F4	4.78	.17	6.42	8.14	64.80			8	25	33	1.67		.11			
545.0	550.0	70913	5.0	.0	2F4	4.72	.07	6.71	9.67	62.30			8	25	33	.07		.11			
550.0	555.0	70914	5.0	.0	2F4	5.14	.16	7.62	7.49	71.20			2	30	33	.09		.09			
555.0	560.0	70915	5.0	.0	2F4	5.30	.07	7.68	9.39	55.70			2	30	33	.05		.08			
560.0	565.0	70916	5.0	.0	2F4	4.88	.10	7.25	9.12	53.50			2	30	33	.08		.08			
565.0	570.0	70917	5.0	.0	2G42	3.46	.26	6.60	7.80	52.60			2	30	33	12.13		.08			
570.0	575.0	70918	5.0	.0	2F4	5.20	.06	6.84	9.79	54.10			4	24	28	.16		.11			
575.0	580.0	70919	5.0	.0	2F40	4.72	.10	7.85	8.81	72.10			4	24	28	6.34		.11			
580.0	585.0	70920	5.0	.0	2F46	4.90	.16	10.28	12.02	114.00			4	24	28	4.67		.11			
585.0	590.0	70921	5.0	.0	2G42	5.00	.09	8.26	9.06	95.40			4	24	28	19.48		.11			
590.0	595.0	70922	5.0	.0	2G42	4.57	.29	4.87	4.74	53.70			4	30	35	14.28		.09			
595.0	600.0	70923	5.0	.0	2F40	5.25	.17	3.72	5.23	39.30			4	30	35	.25		.09			
600.0	605.0	70924	5.0	.0	2F40	4.79	.08	3.95	7.13	38.00			4	30	35	.13		.09			
605.0	610.0	70925	5.0	.0	2F40	4.63	.08	5.15	7.43	45.80			4	30	35	.07		.09			
610.0	615.0	70926	5.0	.0	2A00	2.91	.04	.94	2.31	17.20			3	2	6	.50		.04			
615.0	620.0	70927	5.0	.0	2B4	3.11	.11	1.72	3.32	34.40			3	2	6	.35		.04			
620.0	625.0	70928	5.0	.0	2B40	3.04	.08	1.18	2.80	24.90			3	2	6	.33		.04			
625.0	630.0	70929	5.0	.0	2A00	2.96	.10	.36	.56	9.90			3	2	6	.21		.04			
630.0	635.0	70930	5.0	.0	1D4	2.64	.20	.23	.13	65.80			3	2	5	.14		.07			
635.0	639.0	70931	4.0	.0	1D4	2.79	.05	.02	.22	3.40			3	2	5	.19		.07			

```
DDH: 66004      UTM-N: 9999.7      UTM-E: 14000.0      UTM-ELEV: 4192.7      TOTAL DEPTH: 700.0      SECTION:
RFE:          RFE DIR: 0 PLUNGE ANGLES: 0      0 DHD CALC: 1 SS CALC: 0
```

[illegible]

PAGE: 18

[illegible]

```
DDH: 66008      UTM-N: 9799.6      UTM-E: 13799.0      UTM-ELEV: 4189.5      TOTAL DEPTH: 700.0      SECTION:
RFE:          RFE DIR: 0 PLUNGE ANGLES: 0      0 DHD CALC: 1      SS CALC: 0
```

[illegible]

```
DDH: 66008      UTM-N: 9799.6      UTM-E: 13799.0      UTM-ELEV: 4189.5      TOTAL DEPTH: 700.0      SECTION:
RFE:           RFE DIR: 0 PLUNGE ANGLES: 0      0 DHD CALC: 1 SS CALC: 0
```

[illegible]

DDH: 66022 UTM-N: 9797.9 UTM-E: 14199.0 UTM-ELEV: 4124.1 TOTAL DEPTH: 430.5 SECTION:
RFE: RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Pt %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
215.0	220.0	70556	5.0	.0	****	3.10	.18	.23	.76	10.00			5	15	21	.39		.12			
220.0	225.0	70557	5.0	.0	****	3.79	.06	.64	3.30	15.00			5	15	21	.86		.12			
225.0	230.0	70558	5.0	.0	****	3.90	.22	3.24	3.39	66.00			5	15	21	9.37		.12			
230.0	235.0	70559	5.0	.0	****	3.65	.24	2.48	2.65	68.00			5	15	21	6.46		.12			
235.0	240.0	70560	5.0	.0	****	3.59	.38	4.99	3.62	126.00			6	8	15	7.11		.13			
240.0	245.0	70561	5.0	.0	****	3.09	.22	1.52	.56	86.00			6	8	15	3.19		.13			
245.0	255.0	70562	10.0	.0	****	3.32	.41	3.04	2.38	75.00			6	8	15	6.43		.13			
255.0	260.0	70563	5.0	.0	****	4.19	.24	4.12	3.79	76.00			5	18	23	13.18		.20			
260.0	265.0	70564	5.0	.0	****	4.76	.19	3.14	3.82	42.00			5	18	23	9.14		.20			
265.0	270.0	70565	5.0	.0	****	4.51	.08	4.09	5.26	63.00			5	18	23	33.17		.20			
270.0	275.0	70566	5.0	.0	****	4.78	.08	6.52	7.19	112.00			5	18	23	36.66		.20			
275.0	280.0	70567	5.0	.0	****	4.92	.08	5.00	5.71	66.00			4	25	29	24.12		.10			
280.0	285.0	70568	5.0	.0	****	4.80	.10	4.93	6.93	68.00			4	25	29	28.49		.10			
285.0	290.0	70569	5.0	.0	****	4.63	.18	2.56	4.76	42.00			4	25	29	15.67		.10			
290.0	295.0	70570	5.0	.0	****	4.85	.19	2.07	1.97	27.00			4	25	29	2.59		.10			
295.0	300.0	70571	5.0	.0	****	4.65	.02	3.54	7.56	35.00			2	33	36	27.63		.02			
300.0	305.0	70572	5.0	.0	****	4.81	.16	1.38	1.06	21.00			2	33	36	1.22		.02			
305.0	310.0	70573	5.0	.0	****	4.50	.18	1.02	.67	14.00			2	33	36	.04		.02			
310.0	315.0	70574	5.0	.0	****	4.45	.12	.59	.41	10.00			2	33	36	.05		.02			
315.0	320.0	70575	5.0	.0	****	4.81	.22	3.20	4.85	17.00			6	31	37	.05		.12			
320.0	325.0	70576	5.0	.0	****	4.49	.19	2.55	7.10	10.00			6	31	37	.03		.12			
325.0	330.0	70577	5.0	.0	****	4.42	.38	1.87	4.42	7.00			6	31	37	.05		.12			
330.0	335.0	70578	5.0	.0	****	4.27	.16	1.61	2.15	6.00			6	31	37	.12		.12			
335.0	340.0	70579	5.0	.0	****	4.44	.17	3.64	5.67	6.00			7	29	36	.02		.19			
340.0	345.0	70580	5.0	.0	****	4.52	.24	1.42	3.26	4.00			7	29	36	.01		.19			
345.0	350.0	70581	5.0	.0	****	4.60	.27	9.40	15.15	13.00			7	29	36	.02		.19			
350.0	355.0	70582	5.0	.0	****	4.30	.24	.70	2.21	3.00			7	29	36	.03		.19			
355.0	360.0	70583	5.0	.0	****	4.73	.09	4.67	9.63	21.00			6	30	36	.03		.11			
360.0	365.0	70584	5.0	.0	****	4.50	.42	1.20	1.21	21.90						.03					
365.0	370.0	70585	5.0	.0	****	4.50	.24	2.40	3.65	30.20						.03					
370.0	375.0	70586	5.0	.0	****	4.13	.49	.39	1.70	8.00			6	30	36	.03		.11			
375.0	380.0	70587	5.0	.0	****	4.44	.52	.46	1.54	8.00			7	33	40	.02		.12			
380.0	385.0	70588	5.0	.0	****	4.23	.59	.58	1.10	10.00			7	33	40	.02		.12			
385.0	390.0	70589	5.0	.0	****	4.60	.58	.19	1.24	10.00			7	33	40	.05		.12			
390.0	395.0	70590	5.0	.0	****	4.20	.19	.17	1.54	6.00			7	33	40	.04		.12			
395.0	400.0	70591	5.0	.0	****	4.23	.15	1.01	3.03	11.00			6	31	37	.02		.11			
400.0	405.0	70592	5.0	.0	****	4.27	.19	1.20	2.80	5.50						.02					
405.0	410.0	70593	5.0	.0	****	4.30	.25	1.10	2.92	9.00			6	31	37	.02		.11			
410.0	420.0	70594	10.0	.0	****	4.15	.15	2.99	5.43	8.20						.02					
420.0	425.0	70595	5.0	.0	****	4.15		4.40	8.27	21.90						.02					
425.0	430.5	70596	5.5	.0	****	4.15		4.80	5.19	26.00						.02					

DDH: 66026 UTM-N: 9399.9 UTM-E: 13397.3 UTM-ELEV: 4150.1 TOTAL DEPTH: 500.0 SECTION:
RFE: RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

[illegible]

DDH: 66030 UTM-N: 9793.0 UTM-E: 14536.3 UTM-ELEV: 4124.7 TOTAL DEPTH: 526.0 SECTION:
RFE: RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	ASSAYS														S.G. W.R.
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Pt %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	
215.0	220.0	70621	5.0	.0	****	2.80	.09	1.02	1.43	19.20			7	9	16	1.21		.06			
220.0	225.0	70622	5.0	.0	****	3.06	.18	1.10	6.11	22.70			7	9	16	.64		.06			
225.0	230.0	70623	5.0	.0	****	3.48	.29	4.44	7.31	48.30			7	9	16	.21		.06			
230.0	235.0	70624	5.0	.0	****	3.31	.75	.23	.96	16.00			7	9	16	.17		.06			
235.0	240.0	70625	5.0	.0	****	2.87	.26	.22	.48	9.30			4	6	11	.11		.04			
240.0	245.0	70626	5.0	.0	****	2.75	.01	.04	.06	.90			4	6	11	.14		.04			
245.0	250.0	70627	5.0	.0	****	2.75	.24	.38	.18	18.00			4	6	11	.19		.04			
250.0	255.0	70628	5.0	.0	****	3.35	.36	1.77	1.76	29.20			4	6	11	.07		.04			
255.0	260.0	70629	5.0	.0	****	2.81	.22	1.06	.24	17.30			3	15	18	.12		.03			
260.0	265.0	70630	5.0	.0	****	3.19	.16	.52	1.02	9.90			3	15	18	.09		.03			
265.0	270.0	70631	5.0	.0	****	3.90	.15	.45	1.50	4.80			3	15	18	.08		.03			
270.0	275.0	70632	5.0	.0	****	4.01	.17	1.57	2.45	13.40			3	15	18	.06		.03			
275.0	280.0	70633	5.0	.0	****	3.91	.09	3.00	5.25	20.30			3	7	11	.13		.06			
280.0	285.0	70634	5.0	.0	****	3.02	.10	2.71	6.74	21.00			3	7	11	.18		.06			
285.0	290.0	70635	5.0	.0	****	2.75	.06	.32	.34	8.40			3	7	11	.22		.06			
290.0	295.0	70636	5.0	.0	****	2.79	.03	.21	.27	5.00			3	7	11	.27		.06			
295.0	300.0	70637	5.0	.0	****	3.24	.14	2.87	4.41	26.30			3	16	19	.21		.05			
300.0	305.0	70638	5.0	.0	****	3.54	.17	1.90	4.46	19.50			3	16	19	.10		.05			
305.0	310.0	70639	5.0	.0	****	3.66	.10	2.20	7.35	13.20			3	16	19	.09		.05			
310.0	315.0	70640	5.0	.0	****	3.64	.09	1.99	7.16	13.30			3	16	19	.11		.05			
315.0	320.0	70641	5.0	.0	****	3.67	.04	2.91	5.33	19.60			2	20	22	.14		.02			
320.0	325.0	70642	5.0	.0	****	3.55	.03	3.57	5.80	31.00			2	20	22	.14		.02			
325.0	330.0	70643	5.0	.0	****	3.78	.02	1.48	5.07	14.00			2	20	22	.13		.02			
330.0	335.0	70644	5.0	.0	****	3.67	.02	3.96	6.44	27.00			2	20	22	.19		.02			
335.0	340.0	70645	5.0	.0	****	3.35	.04	1.22	6.73	14.80			2	21	23	.27		.02			
340.0	345.0	70646	5.0	.0	****	4.08	.05	1.82	4.64	16.40			2	21	23	.11		.02			
345.0	350.0	70647	5.0	.0	****	3.83	.02	2.15	5.48	14.60			2	21	23	.10		.02			
350.0	355.0	70648	5.0	.0	****	3.24	.05	2.89	5.86	24.70			2	21	23	.15		.02			
355.0	360.0	70649	5.0	.0	****	3.44	.06	4.37	8.09	33.20			2	15	18	.17		.01			
360.0	365.0	70650	5.0	.0	****	3.40	.05	6.36	12.33	35.20			2	15	18	.12		.01			
365.0	370.0	70651	5.0	.0	****	3.38	.04	.54	2.08	15.50			2	15	18	.15		.01			
370.0	375.0	70652	5.0	.0	****	3.60	.04	.50	2.80	11.50			2	15	18	.11		.01			
375.0	380.0	70653	5.0	.0	****	3.51	.06	3.02	10.11	16.40			2	16	18	.17		.01			
380.0	385.0	70654	5.0	.0	****	3.75	.03	4.26	12.32	18.40			2	16	18	.16		.01			
385.0	390.0	70655	5.0	.0	****	3.35	.06	1.38	2.46	17.50			2	16	18	.20		.01			
390.0	395.0	70656	5.0	.0	****	3.02	.04	.50	.58	8.30			2	16	18	.23		.01			
395.0	400.0	70657	5.0	.0	****	3.10		.08	.35	7.20			1	24	26	.01		.01			
400.0	405.0	70658	5.0	.0	****	3.02	.04	.16	1.11	6.20			1	24	26	.18		.01			
405.0	410.0	70659	5.0	.0	****	3.02	.05	.98	4.93	14.40			1	24	26	.07		.01			
410.0	415.0	70660	5.0	.0	****	3.43	.08	.54	1.61	11.60			1	24	26	.19		.01			
415.0	420.0	70661	5.0	.0	****	3.38	.03	1.78	2.78	18.30			2	14	17	.17		.02			
420.0	425.0	70662	5.0	.0	****	3.31	.02	2.26	6.39	28.60			2	14	17	.20		.02			
425.0	430.0	70663	5.0	.0	****	3.11	.03	1.86	5.38	24.10			2	14	17	.22		.02			
430.0	435.0	70664	5.0	.0	****	3.39	.04	2.20	4.03	25.00			2	14	17	.20		.02			
435.0	440.0	70665	5.0	.0	****	3.38	.04	.56	1.88	11.50			2	29	32	.20		.02			
440.0	445.0	70666	5.0	.0	****	4.64	.01	2.68	6.81	21.80			2	29	32	.06		.02			
445.0	450.0	70667	5.0	.0	****	5.09		6.10	8.36	34.00			2	29	32	.01		.02			
450.0	455.0	70668	5.0	.0	****	4.93		5.08	10.41	37.50			2	29	32	.01		.02			
455.0	460.0	70669	5.0	.0	****	4.63	.01	3.13	12.09	22.10			2	33	35	.02		.01			
460.0	465.0	70670	5.0	.0	****	5.04	.02	5.15	14.81	35.50			2	33	35	.02		.01			
465.0	470.0	70671	5.0	.0	****	4.99		1.20	3.09	13.00			2	33	35	.01		.01			

DDH: 66030 UTM-N: 9793.0 UTM-E: 14536.3 UTM-ELEV: 4124.7 TOTAL DEPTH: 526.0 SECTION:
RFE: RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS----						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
470.0	475.0	70672	5.0	.0	****	4.85	.09	4.63	9.85	42.80			2	33	35	.02		.01			
475.0	480.0	70673	5.0	.0	****	2.98	.23	.84	4.42	22.70			4	4	8	.15		.06			
480.0	485.0	70674	5.0	.0	****	2.69	.07	.68	.06	15.80			4	4	8	.23		.06			
485.0	490.0	70675	5.0	.0	****	2.74	.06	.38	.01	11.90			4	4	8	.17		.06			
490.0	495.0	70676	5.0	.0	****	2.84	.14	2.06	.01	51.00			4	4	8	.14		.06			
495.0	500.0	70677	5.0	.0	****	2.75	.01	.06	.01	1.70			5	5	10	.16		.03			
500.0	505.0	70678	5.0	.0	****	3.06	.14	.68	2.16	19.70			5	5	10	.15		.03			
505.0	510.0	70679	5.0	.0	****	3.10	.17	1.58	6.42	20.00			5	5	10	.21		.03			
510.0	515.0	70680	5.0	.0	****	3.22	.14	2.93	7.54	34.20			5	5	10	.19		.03			
515.0	520.0	70681	5.0	.0	****	3.21	.06	4.93	9.78	45.30			6	5	11	.21		.02			
520.0	526.0	70682	6.0	.0	****	3.22	.12	1.98	6.13	32.90			6	5	11	.16		.02			

DDH: 66031 UTM-N: 9399.6 UTM-E: 13797.3 UTM-ELEV: 4128.0 TOTAL DEPTH: 500.0 SECTION:
 RFE: RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
385.0	390.0	70687	5.0	.0	****	2.63	.11	.61	1.05	8.00			4	3	8	.17		.06			
390.0	395.0	70688	5.0	.0	****	2.70	.11	1.07	.81	14.00			4	3	8	.19		.06			
395.0	400.0	70689	5.0	.0	****	2.61	.07	1.68	2.17	13.00			4	3	8	.33		.06			
400.0	405.0	70690	5.0	.0	****	3.59	.05	3.12	5.58	30.00			9	20	30	.08		.12			
405.0	410.0	70691	5.0	.0	****	4.18	.10	3.35	6.35	43.00			9	20	30	3.37		.12			
410.0	416.0	70692	6.0	.0	****	4.19	.13	4.91	6.97	75.00			9	20	30	7.07		.12			
416.0	423.0	70693	7.0	.0	****	4.29	.24	5.47	7.80	76.00			9	20	30	3.55		.12			
423.0	427.0	70694	4.0	.0	****	4.10	.35	5.90	8.46	86.00			22	11	33	.29		.13			
427.0	430.0	70695	3.0	.0	****	4.20	.27	8.63	9.97	100.00			22	11	33	.19		.13			
430.0	436.0	70696	6.0	.0	****	3.94	.29	7.49	7.92	76.00			22	11	33	.09		.13			
436.0	440.0	70697	4.0	.0	****	3.78	.25	7.10	7.80	66.00			22	11	33	.27		.13			
440.0	446.0	70698	6.0	.0	****	4.67	.11	6.57	6.81	80.00			6	29	36	1.31		.22			
446.0	450.0	70699	4.0	.0	****	4.44	.18	4.53	7.08	53.00			6	29	36	5.13		.22			
450.0	456.0	70700	6.0	.0	****	4.83	.25	5.59	5.83	51.00			6	29	36	.09		.22			
456.0	462.0	70701	6.0	.0	****	4.69	.28	5.25	5.98	43.00			5	28	34	.04		.17			
462.0	465.0	70702	3.0	.0	****	4.71	.17	6.33	6.97	73.00			5	28	34	4.65		.17			
465.0	471.0	70703	6.0	.0	****	4.81	.12	5.75	7.40	60.00			5	28	34	13.94		.17			
471.0	476.0	70704	5.0	.0	****	4.70	.06	5.43	8.15	43.00			5	28	34	.18		.17			
476.0	482.0	70705	6.0	.0	****	4.43	.28	4.54	6.26	57.00			16	7	24	.13		.04			
482.0	490.0	70706	8.0	.0	****	2.71	.06	1.95	2.47	39.00			16	7	24	.15		.04			
490.0	492.0	70707	2.0	.0	****	2.61	.01	.78	1.35	17.00			16	7	24	.05		.04			

DDH: 66033 UTM-N: 9399.3 UTM-E: 14197.3 UTM-ELEV: 4078.6 TOTAL DEPTH: 461.5 SECTION:
 RFE: RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----							-----ASSAYS-----													
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
310.0	315.0	70714	5.0	.0	****	3.20	.12	.93	1.22	19.00		11	10	21	.14		.05			
315.0	320.0	70715	5.0	.0	****	3.21	.26	.29	.12	5.00		11	10	21	.07		.05			
320.0	325.0	70716	5.0	.0	****	3.15	.29	.16	.06	5.00		11	10	21	.08		.05			
325.0	330.0	70717	5.0	.0	****	3.35	.26	2.82	4.98	36.50		11	10	21	.16		.05			
330.0	335.0	70718	5.0	.0	****	4.16	.33	6.61	9.17	77.00		14	10	25	.08		.14			
335.0	340.0	70719	5.0	.0	****	4.04	.31	5.38	8.61	73.00		14	10	25	1.84		.14			
340.0	345.0	70720	5.0	.0	****	3.59	.29	3.40	5.69	65.00		14	10	25	1.48		.14			
345.0	350.0	70721	5.0	.0	****	2.92	.06	1.93	4.62	33.50		14	10	25	.12		.14			
350.0	355.0	70722	5.0	.0	****	3.37	.13	4.51	8.03	57.00		6	19	25	.20		.13			
355.0	360.0	70723	5.0	.0	****	5.26	.06	7.05	11.69	74.50		6	19	25	3.30		.13			
360.0	365.0	70724	5.0	.0	****	4.51	.22	7.72	6.62	106.00		6	19	25	15.15		.13			
365.0	370.0	70725	5.0	.0	****	4.70	.12	5.67	7.58	61.00		6	19	25	17.70		.13			
370.0	375.0	70726	5.0	.0	****	4.78	.21	2.94	4.91	31.00		3	30	33	7.18		.08			
375.0	380.0	70727	5.0	.0	****	4.71	.07	3.96	6.64	42.00		3	30	33	30.05		.08			
380.0	385.0	70728	5.0	.0	****	4.63	.24	4.87	4.12	48.00		3	30	33	4.13		.08			
385.0	390.0	70729	5.0	.0	****	4.73	.30	2.58	2.60	37.00		3	30	33	.08		.08			
390.0	395.0	70730	5.0	.0	****	4.40	.31	6.75	8.06	48.00		5	30	35	.06		.10			
395.0	400.0	70731	5.0	.0	****	4.76	.25	3.67	3.44	42.00		5	30	35	.08		.10			
400.0	405.0	70732	5.0	.0	****	4.59	.18	5.11	4.84	52.00		5	30	35	4.75		.10			
405.0	410.0	70733	5.0	.0	****	4.57	.18	4.83	5.08	37.00		5	30	35	14.36		.10			
410.0	415.0	70734	5.0	.0	****	4.43	.19	1.98	2.25	21.00		3	30	33	2.38		.06			
415.0	420.0	70735	5.0	.0	****	4.59	.07	4.67	7.17	52.00		3	30	33	27.16		.06			
420.0	425.0	70736	5.0	.0	****	4.36	.19	2.61	3.82	21.00		3	30	33	.13		.06			
425.0	430.0	70737	5.0	.0	****	4.75	.25	5.20	11.39	30.00		3	30	33	.03		.06			
430.0	435.0	70738	5.0	.0	****	4.48	.58	1.64	1.56	12.00		3	38	41	.12		.06			
435.0	440.0	70739	5.0	.0	****	4.61	.33	.89	1.13	8.00		3	38	41	.05		.06			
440.0	445.0	70740	5.0	.0	****	5.10	.32	.59	2.07	8.00		3	38	41	.03		.06			
445.0	450.0	70741	5.0	.0	****	4.34	.54	1.42	1.88	11.00		3	38	41	.08		.06			
450.0	455.0	70742	5.0	.0	****	4.58	.33	1.65	3.05	9.00		3	36	39	.02		.05			
455.0	461.5	70743	6.5	.0	****	4.69	.14	3.51	6.33	17.00		3	36	39	.02		.05			

```
DDH: 66035      UTM-N: 10095.8      UTM-E: 14099.6      UTM-ELEV: 4178.9      TOTAL DEPTH: 405.0      SECTION:
RFE:           RFE DIR: 0 PLUNGE ANGLES: 0      0 DHD CALC: 1      SS CALC: 0
```

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	---ASSAYS---													
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Pt %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %
125.0	130.0	70746	5.0	.0	****	.50	.18	1.36	2.90	34.00										
130.0	135.0	70747	5.0	.0	****	.50	.01	5.00	6.82	110.10										
135.0	140.0	70748	5.0	.0	****	.50	.01	3.64	6.48	43.90										
140.0	145.0	70749	5.0	.0	****	.50	.13	1.16	.90	22.30										
145.0	150.0	70750	5.0	.0	****	.50	.22	.23	1.25	25.40										
185.0	190.0	70752	5.0	.0	****	.50	.07	3.02	11.17	34.30										
190.0	195.0	70753	5.0	.0	****	.50	.04	4.36	12.76	34.30										
195.0	200.0	70754	5.0	.0	****	.50	.06	1.34	1.53	15.80										
215.0	220.0	70756	5.0	.0	****	.50	.16	1.81	5.12	22.00										
220.0	225.0	70757	5.0	.0	****	.50	.01	2.09	11.17	20.60										
225.0	230.0	70758	5.0	.0	****	.50	.03	3.71	9.76	34.00										
230.0	235.0	70759	5.0	.0	****	.50	.24	2.02	1.65	23.30										
235.0	240.0	70760	5.0	.0	****	.50	.01	3.63	6.23	27.40										
240.0	245.0	70761	5.0	.0	****	.50	.15	.66	3.99	6.20										
245.0	250.0	70762	5.0	.0	****	.50	.01	4.12	6.87	9.60										
250.0	255.0	70763	5.0	.0	****	.50	.01	4.48	10.14	18.50										
255.0	260.0	70764	5.0	.0	****	.50	.01	6.70	13.89	26.10										
260.0	265.0	70765	5.0	.0	****	.50	.01	6.60	12.83	26.10										
265.0	270.0	70766	5.0	.0	****	.50	.01	4.59	12.12	20.60										
270.0	275.0	70767	5.0	.0	****	.50	.01	2.50	7.21	13.70										
275.0	280.0	70768	5.0	.0	****	.50	.01	3.42	8.34	14.40										
280.0	285.0	70769	5.0	.0	****	.50	.01	2.55	7.70	15.10										
285.0	290.0	70770	5.0	.0	****	.50	.01	.50	1.93	4.80										
290.0	295.0	70771	5.0	.0	****	.50	.01	.30	1.38	4.80										
295.0	300.0	70772	5.0	.0	****	.50	.01	1.64	4.92	6.90										
300.0	305.0	70773	5.0	.0	****	.50	.01	1.29	5.18	4.80										
305.0	310.0	70774	5.0	.0	****	.50	.01	1.52	6.42	9.60										
310.0	315.0	70775	5.0	.0	****	.50	.01	1.76	7.80	13.00										
315.0	320.0	70776	5.0	.0	****	.50	.01	1.86	7.70	10.30										
320.0	325.0	70777	5.0	.0	****	.50	.01	1.57	6.41	14.40										
325.0	330.0	70778	5.0	.0	****	.50	.07	3.90	10.07	28.80										
330.0	335.0	70779	5.0	.0	****	.50	.01	1.70	5.77	23.30										
335.0	340.0	70780	5.0	.0	****	.50	.01	1.60	5.40	12.30										
340.0	345.0	70781	5.0	.0	****	.50	.01	2.37	5.70	6.90										
345.0	350.0	70782	5.0	.0	****	.50	.01	.68	1.90	4.80										
350.0	355.0	70783	5.0	.0	****	.50	.01	2.75	6.75	16.50										
355.0	360.0	70784	5.0	.0	****	3.90	.01	5.85	12.66	41.20										
360.0	365.0	70785	5.0	.0	****	.50	.07	1.47	3.22	4.80										
365.0	370.0	70786	5.0	.0	****	.50	.30	.33	1.33	6.20										
370.0	375.0	70787	5.0	.0	****	.50	.15	.70	3.52	18.90										
385.0	390.0	70789	5.0	.0	****	.50	.15	1.82	6.20	21.30										
390.0	395.0	70790	5.0	.0	****	.50	.27	1.52	5.62	15.80										
395.0	400.0	70791	5.0	.0	****	.50	.15	1.92	5.05	31.60										
400.0	405.0	70792	5.0	.0	****	.50	.03	3.57	8.37	48.00										

[illegible]

DDH: 66057 UTM-N: 9919.0 UTM-E: 14690.0 UTM-ELEV: 4207.8 TOTAL DEPTH: 600.0 SECTION:
 RFE: RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	ASSAYS													
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Pc %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %
295.0	300.0	70957	5.0	.0	****	3.81	.03	.91	3.49	21.90			7	11	19	.10		.06		
300.0	305.0	70958	5.0	.0	****	3.81	.08	1.50	4.23	16.30			7	11	19	.10		.06		
305.0	310.0	70959	5.0	.0	****	3.32	.32	3.06	4.02	40.10			7	11	19	.08		.06		
360.0	365.0	70961	5.0	.0	****	2.77	.18	1.30	.16	34.00			3	18	21	.13		.04		
365.0	370.0	70962	5.0	.0	****	3.45	.33	2.21	.62	40.40			3	18	21	.09		.04		
370.0	375.0	70963	5.0	.0	****	3.04	.06	.76	.50	9.00			3	18	21	.04		.04		
375.0	380.0	70964	5.0	.0	****	3.20	.03	.50	1.68	20.00			3	18	21	.15		.04		
380.0	385.0	70965	5.0	.0	****	3.23	.11	1.54	3.45	16.20			4	7	11	.15		.05		
385.0	390.0	70966	5.0	.0	****	3.12	.10	1.68	4.37	22.20			4	7	11	.17		.05		
390.0	395.0	70967	5.0	.0	****	2.66	.14	1.06	.36	24.00			4	7	11	.10		.05		
395.0	400.0	70968	5.0	.0	****	3.19	.25	1.14	2.48	19.30			4	7	11	.11		.05		
400.0	405.0	70969	5.0	.0	****	3.26	.23	1.88	4.62	24.30			5	11	16	.06		.05		
405.0	410.0	70970	5.0	.0	****	3.47	.06	3.62	11.03	27.00			3	12	16	.14		.04		
410.0	415.0	70971	5.0	.0	****	3.35	.16	.66	2.96	12.20			3	12	16	.14		.04		
415.0	420.0	70972	5.0	.0	****	3.57	.08	2.96	7.80	25.70			3	12	16	.11		.04		
420.0	425.0	70973	5.0	.0	****	3.64	.04	5.10	14.30	34.00			4	9	13	.12		.04		
425.0	430.0	70974	5.0	.0	****	2.89	.23	1.98	3.54	19.70			4	9	13	.13		.04		
430.0	435.0	70975	5.0	.0	****	3.48	.12	5.79	9.02	43.20			4	9	13	.12		.04		
435.0	440.0	70976	5.0	.0	****	3.19	.16	3.52	7.93	23.30			4	9	13	.11		.04		
440.0	445.0	70977	5.0	.0	****	3.33	.07	2.36	6.47	32.90			3	10	14	.11		.03		
445.0	450.0	70978	5.0	.0	****	3.40	.06	4.92	12.00	28.20			3	10	14	.10		.03		
450.0	455.0	70979	5.0	.0	****	3.28	.14	3.52	7.38	28.60			3	10	14	.09		.03		
455.0	460.0	70980	5.0	.0	****	3.47	.07	3.86	9.41	39.90			3	10	14	.11		.03		
460.0	465.0	70981	5.0	.0	****	3.45	.11	1.80	5.08	27.20			5	10	15	.23		.03		
465.0	470.0	70982	5.0	.0	****	3.31	.17	1.90	4.15	28.60			5	10	15	.10		.03		

DDH: 66E-01 UTM-N: 7541.5 UTM-E: 15604.0 UTM-ELEV: 4012.0 TOTAL DEPTH: 452.5 SECTION: 132
RFE: S2 RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS---		-----ASSAYS-----																			
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
150.0	155.0	70988	5.0	.0	2C3	3.05	.14	.10	.16	5.90			7	13	20	.30		.08			
155.0	160.0	70989	5.0	.0	2C3	3.32	.29	.52	.14	16.90			7	13	20	.05		.08			
160.0	165.0	70990	5.0	.0	2D0	3.74	.10	3.25	6.53	60.70		.14	7	13	20	.32		.08			
165.0	170.0	70991	5.0	.0	2D0	3.41	.12	3.13	5.91	53.30		.01	6	11	18	1.76		.17			
170.0	175.0	70992	5.0	.0	2D0	2.92	.04	2.94	3.57	47.40		.01	6	11	18	.40		.17			
175.0	180.0	70993	5.0	.0	2B0	3.17	.12	1.68	2.92	32.70		.01	6	11	18	.28		.17			
180.0	185.0	70994	5.0	.0	2F4	4.45	.14	6.06	10.10	49.10		.01	6	11	18	.08		.17			
185.0	190.0	70995	5.0	.0	2F4	4.93	.06	5.00	9.06	41.50		1.58	10	25	36	.02		.11			
190.0	195.0	70996	5.0	.0	2H4	4.31	.27	4.44	8.85	45.30		.14	10	25	36	.06		.11			
195.0	200.0	70997	5.0	.0	2H34	4.28	.19	2.21	5.97	22.00		.06	10	25	36	.12		.11			

DDH: 66E-04 UTM-N: 7352.0 UTM-E: 15416.0 UTM-ELEV: 4023.0 TOTAL DEPTH: 450.0 SECTION: 132
 RFE: S2 RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----		-----ASSAYS-----																		
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
130.0	135.0	71003	5.0	.0 2D4	3.28	.18	7.49	5.17	133.80		.06	6	16	23	.77		.20			
135.0	140.0	71004	5.0	.0 2C2	3.06	.11	.36	.12	6.80		.01	6	16	23	.38		.20			
140.0	145.0	71005	5.0	.0 2F4	4.04	.14	7.88	6.40	112.50		.14	6	16	23	1.95		.20			
145.0	150.0	71006	5.0	.0 2D0	3.37	.14	5.49	3.95	69.40		.01	6	16	23	.32		.20			
150.0	155.0	71007	5.0	.0 2F4	5.34	.12	4.23	6.10	31.30		.07	6	16	23	.02		.20			
155.0	160.0	71008	5.0	.0 2F4	4.84	.04	4.87	9.96	48.80		.07	7	26	33	.02		.07			
160.0	165.0	71009	5.0	.0 2F4	4.85	.05	6.30	11.33	74.80		.07	7	26	33	.02		.07			
165.0	170.0	71010	5.0	.0 2F4	4.96	.21	4.41	7.63	54.20		.01	7	26	33	.23		.07			
170.0	175.0	71011	5.0	.0 2D0	3.57	.21	2.96	5.06	42.60		.01	7	26	33	.52		.07			
175.0	180.0	71012	5.0	.0 2D0	3.43	.14	1.95	3.42	30.50		.01	11	10	22	1.04		.06			
180.0	185.0	71013	5.0	.0 2C0	3.37	.23	1.28	2.51	19.90		.01	11	10	22	.44		.06			
185.0	190.0	71014	5.0	.0 2H4	3.87	.25	4.18	8.17	71.40		.07	11	10	22	1.63		.06			
190.0	195.0	71015	5.0	.0 2CH	3.11	.10	2.21	3.62	41.50		.01	11	10	22	.55		.06			
195.0	200.0	71016	5.0	.0 2D1	3.22	.09	1.76	2.88	31.30		.14	3	12	15	.52		.06			
200.0	205.0	71017	5.0	.0 2C1	3.10	.06	.37	.69	9.80			3	12	15	.81		.06			
205.0	210.0	71018	5.0	.0 2C1	3.08	.10	.19	1.64	8.00			3	12	15	.54		.06			
210.0	215.0	71019	5.0	.0 2D1	3.25	.10	1.73	4.08	41.30		.21	3	12	15	.67		.06			
215.0	220.0	71020	5.0	.0 2A54	3.26	.09	3.77	4.67	66.20		.21	4	5	10	.68		.04			
220.0	225.0	71021	5.0	.0 2A51	3.21	.11	.98	1.90	30.50		.27	4	5	10	.68		.04			
225.0	230.0	71022	5.0	.0 2A5	2.61		.83	1.32	16.90			4	5	10	.95		.04			
230.0	235.0	71023	5.0	.0 2A5	2.56		.46	.55	6.30			4	5	10	.86		.04			
235.0	240.0	71024	5.0	.0 2A5	2.69		.50	1.30	8.00			5	3	9	.54		.04			
240.0	245.0	71025	5.0	.0 2A5	2.61	.05	.52	1.59	9.40			5	3	9	.37		.04			
245.0	250.0	71026	5.0	.0 2A5	2.93	.31		.32	14.30			5	3	9	.25		.04			

DDH: 66E-05 UTM-N: 7536.0 UTM-E: 15206.0 UTM-ELEV: 4014.0 TOTAL DEPTH: 346.8 SECTION: 130
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----							-----ASSAYS-----													
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
240.0	245.0	71033	5.0	.0 *****	3.02	.16		.01	5.50			5	18	23	.33		.09			
245.0	250.0	71034	5.0	.0 2C8	3.15	.10	.88	1.91	15.30			5	18	23	.38		.09			
250.0	255.0	71035	5.0	.0 2CA	3.02		.81	1.20	13.60			5	18	23	.94		.09			
255.0	260.0	71036	5.0	.0 2E14	3.38	.24	2.25	4.18	32.20		.07	5	18	23	.35		.09			
260.0	265.0	71037	5.0	.0 2E80	3.59	.61	1.30	1.92	23.20		.01	5	18	23	.05		.09			
265.0	270.0	71038	5.0	.0 2E80	4.72	.20	2.01	1.36	25.30		.01	5	36	41	.06		.15			
270.0	275.0	71039	5.0	.0 2E84	4.76	.07	1.72	3.03	20.70		.01	5	36	41	.03		.15			
275.0	280.0	71040	5.0	.0 2E84	4.67	.05	2.25	3.60	21.20		.01	5	36	41	.02		.15			
280.0	285.0	71041	5.0	.0 2E84	4.78		2.77	5.18	25.30		.07	5	36	41	.02		.15			
285.0	290.0	71042	5.0	.0 2E4	4.10	.39	2.27	4.73	31.50		.07	30	14	44	.14		.05			
290.0	295.0	71043	5.0	.0 2H4	4.08	.73	2.01	3.62	37.60		.07	30	14	44	.07		.05			
295.0	300.0	71044	5.0	.0 2H0	3.90	.57	.97	2.41	34.10		.07	30	14	44	.05		.05			
300.0	305.0	71045	5.0	.0 2H0	3.92	.49	1.43	2.55	47.30		.07	30	14	44	.06		.05			
305.0	310.0	71046	5.0	.0 2C0	2.90	.16	.41	2.35	13.00		.01	7	7	15	.27		.11			
310.0	315.0	71047	5.0	.0 2D0	2.88	.13	1.82	4.48	30.60		.07	7	7	15	.20		.11			
315.0	320.0	71048	5.0	.0 2D4	3.34	.24	7.86	12.25	116.80		.01	7	7	15	.18		.11			
320.0	325.0	71049	5.0	.0 2D0	3.05	.07	2.14	4.27	70.10			7	7	15	.49		.11			
325.0	330.0	71050	5.0	.0 2A0	2.61	.02	.83	1.50	17.50			2	1	3	.88		.03			
330.0	335.0	71051	5.0	.0 2A0	2.69	.03	.87	1.23	18.50			2	1	3	.62		.03			
335.0	340.0	71052	5.0	.0 2A0	2.54	.01	.54	1.54	11.40			2	1	3	.77		.03			
340.0	345.0	71053	5.0	.0 2A0	2.69	.03	.78	1.82	22.20			2	1	3	.35		.03			

DDH: 66E-06 UTM-N: 7736.4 UTM-E: 15399.4 UTM-ELEV: 4008.8 TOTAL DEPTH: 500.0 SECTION: 130
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

---DEPTHS---						---ASSAYS---															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
205.0	210.0	71057	5.0	.0	2A4	3.52	.09	1.93	3.38	8.00				2	21	24	.03				.04
210.0	215.0	71058	5.0	.0	2C0	3.45	.07	.47	2.86	4.50				2	21	24	.04				.04
215.0	220.0	71059	5.0	.0	2D0	3.59	.03	1.76	5.85	14.60				2	21	24	.11				.04
220.0	225.0	71060	5.0	.0	2D0	3.28	.09	4.07	4.44	56.70				8	9	18	7.01				.40
225.0	230.0	71061	5.0	.0	2D4	3.99	.13	10.35	8.13	137.90				8	9	18	1.64				.40
230.0	235.0	71062	5.0	.0	2D0	2.98	.04	2.44	2.26	31.50				8	9	18	2.45				.40
235.0	240.0	71063	5.0	.0	2E0	3.37	.07	3.76	2.22	52.00				8	9	18	5.59				.40
240.0	245.0	71064	5.0	.0	1D4/9	2.99	.06	1.25	1.22	21.70		.01	8	15	24	4.48				.13	
245.0	250.0	71065	5.0	.0	1D4	2.75	.04	.66	.95	17.60		.06	8	15	24	2.34				.13	
250.0	255.0	71066	5.0	.0	2J3	4.31	.31	2.94	5.90	38.30			8	15	24	.50				.13	
255.0	260.0	71067	5.0	.0	2J3	4.31	.24	2.41	5.05	33.60			8	15	24	.04				.13	
260.0	265.0	71068	5.0	.0	2J3	4.33	.36	2.58	4.35	31.90			6	25	32	.04				.07	
265.0	275.0	71069	10.0	.0	2F0	4.82	.12	2.97	6.01	18.50			6	25	32	.02				.07	
275.0	280.0	71070	5.0	.0	2D0	2.95	.04	2.10	4.03	20.30		.06	6	25	32	.54				.07	
280.0	285.0	71071	5.0	.0	2D0	2.86	.02	2.48	5.33	27.70		.06	5	9	15	.59				.04	
285.0	290.0	71072	5.0	.0	2D0	3.53	.21	3.90	5.04	51.00		.20	5	9	15	.13				.04	
290.0	295.0	71073	5.0	.0	2D0	2.95	.02	1.07	4.46	22.10		.14	5	9	15	.43				.04	
295.0	300.0	71074	5.0	.0	2D0	2.94	.03	1.42	4.64	26.50		.14	5	9	15	.31				.04	
300.0	305.0	71075	5.0	.0	2A4	2.78	.02	1.30	2.77	25.90		.34	3	2	6	.21				.02	
305.0	311.0	71076	6.0	.0	2D0	3.05	.07	1.92	3.72	34.70		.34	3	2	5	.13				.01	

DDH: 66E-07 UTM-N: 7131.0 UTM-E: 15217.0 UTM-ELEV: 4018.0 TOTAL DEPTH: 504.0 SECTION: 132
RFE: S2 RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS----				-----ASSAYS-----																
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULF	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Pt %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
215.0	220.0	71082	5.0	.0 2B0	2.90	.06	.22	.20	10.40			3	3	7	.49		.04			
220.0	225.0	71083	5.0	.0 2D4	3.03	.07	3.62	7.28	60.30		.07	3	3	7	.11		.04			
225.0	230.0	71084	5.0	.0 2C5	2.85	.05	2.65	1.66	37.00		.07	3	3	7	.18		.04			
230.0	231.6	71085	1.6	.0 2A4	2.97	.04	1.86	3.17	30.20		.07	6	5	11	.45		.14			
231.6	236.0	71086	4.4	.0 2C0	2.83	.03	.76	1.48	12.30		.07	6	5	11	.38		.14			
236.0	241.0	71087	5.0	.0 2A4	3.08	.03	1.55	3.35	29.00		.14	6	5	11	.39		.14			
241.0	245.0	71088	4.0	.0 2D4	3.98	.12	5.52	11.38	97.70		.07	6	5	11	.07		.14			
245.0	250.0	71089	5.0	.0 2D4	3.02	.06	10.62	14.65	197.50		.14	6	5	11	.17		.14			

DDH: 66E-09 UTM-N: 7943.0 UTM-E: 15592.0 UTM-ELEV: 4037.0 TOTAL DEPTH: 546.0 SECTION: 130
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----		-----ASSAYS-----																			
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
230.0	234.0	71101	4.0	.0	2CE	3.13	.28		.27	6.30				3 17	20	.17		.05			
234.0	240.0	71102	6.0	.0	2D4	3.97	.03	5.73	11.14	33.60		1.37	3 17	20	.11			.05			
285.0	290.0	71104	5.0	.0	2E0	3.08	.25	.87	.21	23.10			10 25	36	.30			.18			
290.0	295.0	71105	5.0	.0	2E0	4.04	.25	.01		5.00			10 25	36	.03			.18			
295.0	300.0	71106	5.0	.0	2E0	3.46	1.03	.87	.65	39.00			10 25	36	.05			.18			
300.0	310.0	71107	10.0	.0	1D/2E	3.76	.42	3.97	2.11	87.00		1.78	10 25	36	3.09			.18			
310.0	315.0	71108	5.0	.0	2E4	3.57	.20	2.39	1.95	35.80		.34	7 32	40	.05			.33			
315.0	320.0	71109	5.0	.0	2E84	4.63	.24	2.48	2.37	27.30		.82	7 32	40	.03			.33			
320.0	325.0	71110	5.0	.0	2E84	4.95	.27	3.46	2.22	38.30		.41	7 32	40	.02			.33			
325.0	330.0	71111	5.0	.0	2E1	3.41	.27	1.15	.69	13.40		.27	7 32	40	.08			.33			
330.0	335.0	71112	5.0	.0	2B0	4.80	.23	.45		8.10		.14	2 39	41	.06			.06			
335.0	340.0	71113	5.0	.0	2E4	4.81	.19	2.52	2.65	22.90		.07	2 39	41	.04			.06			
340.0	345.0	71114	5.0	.0	2E0	4.76	.26	1.18	.78	22.80		.07	2 39	41	.04			.06			
345.0	350.0	71115	5.0	.0	2E4	4.83	.15	3.08	4.28	28.70		.07	2 39	41	.03			.06			
350.0	355.0	71116	5.0	.0	2E4	4.32	.18	2.95	5.39	29.10		.07	1 32	34	.03			.06			
355.0	360.0	71117	5.0	.0	2CE	3.80	.08	1.91	.39	27.40			1 32	34	.02			.06			
360.0	365.0	71118	5.0	.0	2E0	4.39	.10	1.08	.71	12.50			1 32	34	.02			.06			
365.0	370.0	71119	5.0	.0	2E0	3.91	.14	.52	.50	11.20			1 32	34	.02			.06			
370.0	375.0	71120	5.0	.0	2C0	3.17	.08	.78	2.42	9.90		.21	1 26	27	.15			.02			
375.0	380.0	71121	5.0	.0	2F4	4.09	.05	5.41	8.10	38.10		.14	1 26	27	.08			.02			
380.0	385.0	71122	5.0	.0	2CE	3.91	.21	1.54	2.11	17.60		.07	1 26	27	.08			.02			
385.0	390.0	71123	5.0	.0	2CE4	4.23	.20	2.08	3.17	19.00		.07	1 26	27	.11			.02			
390.0	395.0	71124	5.0	.0	2CE	4.01	.42	.62	1.00	9.00		.07	5 28	34	.02			.21			
395.0	400.0	71125	5.0	.0	2C0	4.20	.43	.39	1.00	9.10		1.10	5 28	34	.04			.21			
400.0	405.0	71126	5.0	.0	2D0	4.36	.36	1.87	2.32	13.60		.07	5 28	34	.01			.21			
405.0	410.0	71127	5.0	.0	2D0	3.86	.25	3.04	3.46	17.90			5 28	34	.03			.21			
410.0	415.0	71128	5.0	.0	2E8	4.12	.27	1.13	1.81	9.30		.01	4 25	30	.03			.19			
415.0	420.0	71129	5.0	.0	2CE4	3.71	.19	2.20	4.07	13.10			4 25	30	.04			.19			
420.0	425.0	71130	5.0	.0	2CE4	3.43	.08	.57	5.07	6.60			4 25	30	.15			.19			
425.0	430.0	71131	5.0	.0	2CE	4.15	.30	.41	1.73	7.50			4 25	30	.04			.19			
430.0	435.0	71132	5.0	.0	2CE4	3.79	.14	1.34	3.48	8.00		.03	3 24	27	.03			.07			
435.0	440.0	71133	5.0	.0	2EC4	3.81	.06	3.49	8.02	18.50		.03	3 24	27	.11			.07			
440.0	446.5	71134	6.5	.0	2EC4	4.16	.09	4.17	10.35	15.80		.03	3 24	27	.04			.07			

DDH: 67-02 UTM-N: 8171.5 UTM-E: 15753.1 UTM-ELEV: 4123.0 TOTAL DEPTH: 606.0 SECTION: 130
RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS----		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %
438.5	444.0	71146	5.5	.0	2DE	2.79	.09	1.79	2.94	13.10		.07	4	19	23	.04		.05		
444.0	448.5	71147	4.5	.0	2DE	3.30	.11	3.37	10.02	20.20		.14	4	19	23	.09		.05		

DDH: 67-03 UTM-N: 8177.1 UTM-E: 14934.9 UTM-ELEV: 4039.0 TOTAL DEPTH: 999.0 SECTION: 126
 RFE: S2 RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
439.0	444.0	71156	5.0	.0	2C0	2.93	.07	1.64	.11	32.90			5	7	12	.68		.16			
444.0	449.0	71157	5.0	.0	2D4	3.41	.10	4.33	6.28	48.90		.27	5	7	12	.24		.16			
449.0	454.0	71158	5.0	.0	2B4	3.90	.20	3.25	8.38	41.40		.62	4	19	24	.23		.17			
454.0	459.0	71159	5.0	.0	2EG	4.65	.04	4.94	6.66	66.60		2.54	4	19	24	16.04		.17			
459.0	464.0	71160	5.0	.0	2G4	4.62	.14	8.08	7.00	115.40		.01	4	19	24	21.96		.17			
464.0	469.0	71161	5.0	.0	2G/1D	3.83	.03	2.83	4.68	46.00		.07	4	19	24	26.51		.17			
509.0	514.0	71164	5.0	.0	2B0	3.14	.05	2.09	2.26	31.20		.07	14	13	28	7.05		.21			
514.0	519.0	71165	5.0	.0	2B4	4.03	.16	5.00	6.45	79.40		.07	14	13	28	2.97		.21			
519.0	524.0	71166	5.0	.0	2D4	3.97	.20	4.50	7.05	67.40		.01	14	13	28	.64		.21			
524.0	529.0	71167	5.0	.0	2H4	4.34	.25	6.18	9.90	68.50		.01	14	13	28	.07		.21			
529.0	534.0	71168	5.0	.0	2E4	4.34	.25	5.20	9.88	53.20		.07	17	23	40	.03		.22			
534.0	539.0	71169	5.0	.0	2H8	4.53	.12	2.29	1.52	36.20		.01	17	23	40	.04		.22			
539.0	544.0	71170	5.0	.0	2H8	4.36	.27	1.07	1.02	16.30		.01	17	23	40	.04		.22			
544.0	549.0	71171	5.0	.0	2E0	4.59	.13	1.66	1.61	16.60		.01	17	23	40	.03		.22			
549.0	554.0	71172	5.0	.0	2E4	4.55	.07	5.49	9.65	52.30		.07	8	22	31	.02		.09			
554.0	559.0	71173	5.0	.0	2EH	4.74	.21	5.70	9.84	38.20		.07	8	22	31	.02		.09			
559.0	564.0	71174	5.0	.0	2HF	4.90	.12	5.06	9.59	34.70		.07	8	22	31	.03		.09			
564.0	569.0	71175	5.0	.0	2C0	3.34	.13	.72	1.36	9.80		.07	8	22	31	.25		.09			
569.0	574.0	71176	5.0	.0	2C0	3.61	.05	1.09	1.02	60.70		.62	3	23	27	.25		.14			
574.0	579.0	71177	5.0	.0	2D0	3.54	.03	1.11	3.79	17.20		.27	3	23	27	.27		.14			
579.0	584.0	71178	5.0	.0	2F4	4.18	.24	5.45	10.90	40.60		.01	3	23	27	.04		.14			
584.0	589.0	71179	5.0	.0	2F0	4.12	.13	2.33	7.56	33.40		.07	3	23	27	.04		.14			
589.0	594.0	71180	5.0	.0	2D0	3.46	.21	2.32	4.46	25.40		.07	11	11	22	.28		.08			
594.0	599.0	71181	5.0	.0	2ED	3.07	.14	3.18	6.11	25.00		.14	11	11	22	.31		.08			
599.0	604.0	71182	5.0	.0	2H4	3.69	.10	1.71	6.31	38.90		.07	11	11	22	.06		.08			
604.0	609.0	71183	5.0	.0	2A4	3.54	.06	1.19	4.63	28.10		.07	11	11	22	.27		.08			
609.0	614.0	71184	5.0	.0	2A4	3.05	.08	1.24	2.88	18.80		.07	4	5	10	.16		.03			
614.0	619.0	71185	5.0	.0	2A4	2.84	.04	1.45	4.95	22.70		.01	4	5	10	.21		.03			
619.0	624.0	71186	5.0	.0	2A0	2.77	.08	.72	2.78	21.80		.07	4	5	10	.20		.03			
624.0	629.0	71187	5.0	.0	2A0	2.92	.09	1.10	1.75	18.10			4	5	10	.17		.03			

DDH: 67-04 UTM-N: 8162.6 UTM-E: 15361.3 UTM-ELEV: 4081.0 TOTAL DEPTH: 742.0 SECTION: 128
 RFE: 52 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	ASSAYS													
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %
419.0	424.0	71197	5.0	.0	2CF	3.90	.20	.16	4.35	26.60		.21	3	29	32	.23		.04		
424.0	429.0	71198	5.0	.0	2CE4	4.37	.04	2.64	4.85	5.50		.14	3	29	32	.08		.04		
429.0	434.0	71199	5.0	.0	2F1	4.03	.07	.37	6.40	24.80		.27	3	29	32	.14		.04		
434.0	439.0	71200	5.0	.0	1D4	2.77	.12	1.51	1.23	7.30		.14	3	7	11	.50		.12		
439.0	444.0	71201	5.0	.0	1D4	3.15	.07	1.56	2.98	27.30		.48	3	7	11	6.88		.12		
444.0	449.0	71202	5.0	.0	1D4	2.75	.03	.56	.18	4.00			3	7	11	2.27		.12		
449.0	454.0	71203	5.0	.0	1D4	2.72	.04	.78	.95	9.80			3	7	11	9.88		.12		
454.0	459.0	71204	5.0	.0	2DE	3.10	.06	2.68	2.34	14.90		.07	4	18	22	5.03		.12		
459.0	464.0	71205	5.0	.0	2EG	4.49	.02	1.93	5.39	37.00		.21	4	18	22	11.22		.12		
464.0	469.0	71206	5.0	.0	2DE	3.90	.05	1.77	4.40	31.30		.27	4	18	22	.71		.12		
469.0	474.0	71207	5.0	.0	1D4	3.03	.14	.79	.50	15.30		.07	4	18	22	1.54		.12		
474.0	479.0	71208	5.0	.0	1D4	2.94	.07	.74	1.06	14.10		.01	7	24	31	.90		.18		
479.0	484.0	71209	5.0	.0	2E3	3.54	.35	1.56	1.77	32.50			7	24	31	.24		.18		
484.0	489.0	71210	5.0	.0	2E1	4.43	.21	1.07	1.45	18.20		.62	7	24	31	.21		.18		
489.0	494.0	71211	5.0	.0	2CE	4.65	.23	2.14	1.77	23.50		.21	7	24	31	.13		.18		
494.0	499.0	71212	5.0	.0	2E4	5.29	.23	4.34	3.85	37.50		.21	3	39	42	.03		.10		
499.0	504.0	71213	5.0	.0	2E0	4.81	.13	2.23	1.71	20.30		.07	3	39	42	.05		.10		
504.0	509.0	71214	5.0	.0	2E4	5.02	.22	3.00	2.19	24.90		.01	3	39	42	.03		.10		
509.0	514.0	71215	5.0	.0	2E0	4.97	.14	2.09	1.58	24.90		.27	3	39	42	.03		.10		
514.0	519.0	71216	5.0	.0	2E0	5.02	.22	1.23	.85	20.60		.27	4	37	41	.02		.13		
519.0	524.0	71217	5.0	.0	2E4	4.62	.18	2.25	1.90	28.30		.21	4	37	41	.02		.13		
524.0	529.0	71218	5.0	.0	2E04	4.74	.20	2.62	3.16	35.80		.14	4	37	41	.02		.13		
529.0	534.0	71219	5.0	.0	2F0	4.76	.18	2.94	4.55	31.70		.07	4	37	41	.02		.13		
534.0	539.0	71220	5.0	.0	2E4	5.44	.14	6.57	4.33	50.60			2	31	33	.02		.03		
539.0	544.0	71221	5.0	.0	2CE	3.91	.03	1.36	.81	11.10		.27	2	31	33	.02		.03		
544.0	549.0	71222	5.0	.0	2E4	4.16	.10	3.62	5.13	26.30		.21	2	31	33	.03		.03		
549.0	554.0	71223	5.0	.0	2E4	4.36	.19	1.96	3.36	14.30			2	31	33	.03		.03		
554.0	559.0	71224	5.0	.0	2E0	4.01	.45	1.44	1.97	19.20		.14	6	27	33	.02		.27		
559.0	564.0	71225	5.0	.0	2F14	5.20	.25	6.28	10.60	40.10		.07	6	27	33	.02		.27		
564.0	569.0	71226	5.0	.0	2E4	5.05	.22	5.48	7.75	31.60		.01	6	27	33	.02		.27		
569.0	574.0	71227	5.0	.0	2CE	4.18	.35	.55	1.39	9.00		.07	6	27	33	.02		.27		
574.0	579.0	71228	5.0	.0	2CE	3.82	.28	1.86	1.90	18.40		.14	5	26	32	.04		.21		
579.0	584.0	71229	5.0	.0	2CE	3.65	.18	.46	1.55	7.80		.07	5	26	32	.06		.21		
584.0	589.0	71230	5.0	.0	2EC	3.95	.28	.15	1.53	5.20		.01	5	26	32	.13		.21		
589.0	594.0	71231	5.0	.0	2F1	4.43	.15	2.51	4.88	8.10		.01	5	26	32	.03		.21		
594.0	599.0	71232	5.0	.0	2D4	3.90	.14	4.24	8.17	17.60			8	16	24	.07		.06		
599.0	604.0	71233	5.0	.0	2D0	3.55	.12	.75	2.56	6.00			8	16	24	.10		.06		
604.0	609.0	71234	5.0	.0	2D4	3.99	.13	4.10	9.52	23.60			8	16	24	.10		.06		
609.0	614.0	71235	5.0	.0	2F4	4.09	.04	5.38	12.00	16.00			8	16	24	.09		.06		
614.0	619.0	71236	5.0	.0	2F4	4.09	.05	7.04	14.50	18.20			3	20	24	.09		.02		
619.0	624.0	71237	5.0	.0	2F4	4.15	.06	6.34	12.40	18.80			3	20	24	.10		.02		
624.0	629.0	71238	5.0	.0	2F4	4.21	.06	5.77	14.20	20.00			3	20	24	.10		.02		
629.0	634.0	71239	5.0	.0	2F4	4.55	.07	6.78	16.50	27.00			3	20	24	.04		.02		
634.0	639.0	71240	5.0	.0	2F4	4.35	.03	7.61	10.70	42.20			12	14	26	.03		.05		
639.0	644.0	71241	5.0	.0	2E4	4.43	.64	3.14	5.97	24.30			12	14	26	.03		.05		
644.0	649.0	71242	5.0	.0	2H4	3.20	.08	2.29	1.85	28.80			12	14	26	.19		.05		

DDH: 67-05 UTM-N: 7942.0 UTM-E: 15176.7 UTM-ELEV: 4028.0 TOTAL DEPTH: 569.0 SECTION: 128
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----		-----ASSAYS-----																			
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
308.0	313.0	71249	5.0	.0	2DE	3.44	.09	3.58	4.67	56.10		.07	12	12	25	1.60		.09			
313.0	318.0	71250	5.0	.0	2DE4	4.07	.21	3.66	7.95	57.60		.07	12	12	25	.62		.09			
360.0	365.0	71252	5.0	.0	2D6	3.29	.09	1.84	2.63	31.50		.01	30	7	38	10.66		.06			
365.0	370.0	71253	5.0	.0	2H4	4.51	.21	7.13	11.30	74.30			30	7	38	.15		.06			
370.0	375.0	71254	5.0	.0	2H4	4.59	.18	7.00	14.00	68.10		.07	30	7	38	.02		.06			
375.0	380.0	71255	5.0	.0	2H4	4.22	.22	2.20	5.86	30.60		.07	30	7	38	.05		.06			
380.0	385.0	71256	5.0	.0	2C0	3.42	.16	.61	.76	17.10			22	8	31	.02		.05			
385.0	390.0	71257	5.0	.0	2C0	3.35	.14	.55	.62	10.50			22	8	31	.07		.05			
390.0	395.0	71258	5.0	.0	2DH	3.81	.19	1.82	3.93	24.50		.07	22	8	31	.11		.05			
395.0	400.0	71259	5.0	.0	2D7	3.63	.45	1.40	3.27	21.00		.41	22	8	31	.23		.05			
400.0	405.0	71260	5.0	.0	2H4	4.11	.28	1.86	3.86	23.40		.27	30	12	43	.09		.17			
405.0	410.0	71261	5.0	.0	2H4	4.10	.26	1.53	3.52	30.00		.01	30	12	43	.02		.17			
410.0	415.0	71262	5.0	.0	2HF4	4.39	.26	4.59	10.20	40.90		.01	30	12	43	.15		.17			
415.0	420.0	71263	5.0	.0	2F4	4.42	.13	4.50	8.15	41.50		.07	30	12	43	.03		.17			
420.0	425.0	71264	5.0	.0	2F4	4.29	.16	5.21	9.17	38.50			5	30	35	.03		.17			
425.0	430.0	71265	5.0	.0	2FE	4.44	.16	3.68	5.58	26.10		.07	5	30	35	.05		.17			
430.0	435.0	71266	5.0	.0	2E84	3.90	.11	.94	2.13	8.40		.01	5	30	35	.03		.17			
435.0	440.0	71267	5.0	.0	2F0	3.27	.08	1.89	4.93	8.60		.07	5	30	35	.05		.17			
440.0	445.0	71268	5.0	.0	2H4	2.85	.24	2.46	5.74	10.80		.01	13	10	23	.04		.06			
445.0	450.0	71269	5.0	.0	2D0	3.79	.27	2.96	5.76	22.40		.07	13	10	23	.11		.06			
450.0	455.0	71270	5.0	.0	2A4	3.15	.07	2.68	7.89	36.40		.14	13	10	23	.26		.06			
455.0	460.0	71271	5.0	.0	2D0	3.02	.06	1.59	4.54	26.20		.01	13	10	23	.39		.06			
460.0	465.0	71272	5.0	.0	2C0	3.09	.21	1.04	2.18	16.30			8	11	20	.34		.06			
465.0	470.0	71273	5.0	.0	2EA	3.36	.14	2.35	4.82	32.50		.07	8	11	20	.22		.06			
470.0	475.0	71274	5.0	.0	2DE	3.50	.23	2.77	4.80	44.10		.07	8	11	20	.13		.06			
475.0	480.0	71275	5.0	.0	2DE	3.33	.12	1.47	3.04	28.50		.14	8	11	20	.13		.06			
480.0	485.0	71276	5.0	.0	2A4	3.02	.09	1.38	3.95	29.60		.14	4	3	7	.18		.04			
485.0	490.0	71277	5.0	.0	2A0	2.75	.08	.98	1.30	23.70			4	3	7	.24		.04			

DDH: 67-06 UTM-N: 8566.2 UTM-E: 15016.0 UTM-ELEV: 4135.0 TOTAL DEPTH: 852.5 SECTION: 124
 RFE: S2 RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
485.0	490.0	71285	5.0	.0	2A0	3.12	.17	.13	.30	6.30			3	16	19	.22		.08			
490.0	495.0	71286	5.0	.0	2EA	4.20	.21	.03	.14	4.60			3	16	19	.02		.08			
495.0	500.0	71287	5.0	.0	2A0	3.10	.16	.11	1.34	7.50			3	16	19	.09		.08			
500.0	505.0	71288	5.0	.0	2A0	2.79	.14	.07	.25	4.70			3	16	19	.14		.08			
505.0	510.0	71289	5.0	.0	2A0	2.96	.11	.12	.91	5.80			3	12	15	.38		.09			
510.0	515.0	71290	5.0	.0	2C0	3.57	.14	.88	1.16	10.90			3	12	15	.11		.09			
515.0	520.0	71291	5.0	.0	2C0	3.10	.02	.08	.69	1.70			3	12	15	.37		.09			
588.0	593.0	71293	5.0	.0	2F0	4.33	.11	4.70	7.80	60.50			6	15	21	6.36		.10			
593.0	598.0	71294	5.0	.0	1D/2E	3.33	.18	2.58	2.61	39.40			6	15	21	4.93		.10			
598.0	603.0	71295	5.0	.0	1D4	3.59	.11	2.48	3.09	50.90			6	15	21	8.09		.10			
603.0	608.0	71296	5.0	.0	2GE	3.95	.18	2.98	4.12	55.00			6	15	21	16.56		.10			
608.0	613.0	71297	5.0	.0	2D0	4.25	.17	4.40	3.45	84.10			3	29	33	3.15		.12			
613.0	618.0	71298	5.0	.0	2C0	4.36	.18	2.13	.83	55.70			3	29	33	.13		.12			
618.0	623.0	71299	5.0	.0	2D0	3.89	.11	4.10	4.62	52.90			3	29	33	.06		.12			
623.0	628.0	71300	5.0	.0	2D0	5.59	.10	2.74	3.57	33.80			3	29	33	5.28		.12			
628.0	633.0	71301	5.0	.0	2CG	4.71	.01	2.94	4.15	36.10				28	28	2.31		.01			
633.0	638.0	71302	5.0	.0	2C0	4.37	.01	.60	1.14	7.90				28	28	1.69		.01			
638.0	643.0	71303	5.0	.0	2C0	3.76	.01	.09	.11	2.60				28	28	.06		.01			
643.0	648.0	71304	5.0	.0	2C0	3.12	.01	.05	.10	3.30				28	28	.03		.01			
648.0	653.0	71305	5.0	.0	2C0	3.53		.06	.10	3.30				28	28	.02		.03			
653.0	658.0	71306	5.0	.0	2C0	3.48	.01	.06	.10	3.00				28	28	.02					
658.0	663.0	71307	5.0	.0	2C0	3.99	.16	.05	.10	3.10				28	28	.03					
663.0	668.0	71308	5.0	.0	2GE	4.65	.08	1.70	2.38	16.70		.07		28	28	.07		.03			
668.0	673.0	71309	5.0	.0	2G4	4.73	.08	3.71	6.63	29.20		.01	3	27	31	19.61		.17			
673.0	678.0	71310	5.0	.0	2F64	4.61	.07	4.80	8.06	38.40		.14	3	27	31	4.55		.17			
678.0	683.0	71311	5.0	.0	2GE4	4.89	.08	4.95	7.78	48.80		.07	3	27	31	12.57		.17			
683.0	688.0	71312	5.0	.0	2E4	4.68	.24	3.73	4.70	44.00		.21	3	27	31	.17		.17			
688.0	693.0	71313	5.0	.0	2E4	4.73	.16	2.65	1.97	25.80		.07	1	33	35	.04		.05			
693.0	698.0	71314	5.0	.0	2E4	5.10	.10	4.45	2.93	42.30		.07	1	33	35	.02		.05			
698.0	703.0	71315	5.0	.0	2E0	4.74	.17	2.39	1.29	23.60		.21	1	33	35	.04		.05			
703.0	708.0	71316	5.0	.0	2C0	4.48	.01	.30	.12	7.90		.07	1	33	35	.02		.05			
708.0	713.0	71317	5.0	.0	2C0	4.30	.01	.34	.32	6.30		.07	1	31	33	.02		.08			
713.0	718.0	71318	5.0	.0	2G0	4.68	.03	3.64	5.41	38.70		.01	1	31	33	14.99		.08			
718.0	723.0	71319	5.0	.0	2EF	4.83	.12	2.58	2.98	34.20		.07	1	31	33	1.48		.08			
723.0	728.0	71320	5.0	.0	2EF	4.85	.20	2.70	2.75	43.30		.14	1	31	33	.05		.08			
728.0	733.0	71321	5.0	.0	2EF	4.51	.08	4.54	6.26	35.60		.07	4	30	34	.04		.14			
733.0	738.0	71322	5.0	.0	2E0	4.38	.21	2.15	2.75	15.20		.01	4	30	34	.03		.14			
738.0	743.0	71323	5.0	.0	2EC	3.67	.28	1.27	2.66	13.30		.07	4	30	34	.03		.14			
743.0	748.0	71324	5.0	.0	2C0	4.80	.22	.83	2.43	9.70		.75	4	30	34	.02		.14			
748.0	753.0	71325	5.0	.0	2F0	4.77	.16	4.36	10.80	19.00		.41	5	21	26	.02		.12			
753.0	758.0	71326	5.0	.0	2D0	4.39	.21	2.54	7.03	14.60		.21	5	21	26	.02		.12			
758.0	763.0	71327	5.0	.0	2D4	4.28	.12	3.80	9.81	25.30		.14	5	21	26	.02		.12			
763.0	768.0	71328	5.0	.0	2A0	2.74	.09	1.13	2.31	15.20		.07	5	21	26	.26		.12			
768.0	773.0	71329	5.0	.0	2A0	2.81	.06	1.14	2.12	17.70		.07	6	3	9	.32		.10			
773.0	778.0	71330	5.0	.0	2A4	2.75	.06	1.29	3.69	21.00		.21	6	3	9	.24		.10			
778.0	783.0	71331	5.0	.0	2A4	3.18	.28	5.67	5.36	74.00		.41	6	3	9	.19		.10			

DDH: 67-07 UTM-N: 7743.1 UTM-E: 15007.0 UTM-ELEV: 4005.0 TOTAL DEPTH: 551.0 SECTION: 128
RFE: S2 RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

---DEPTHS---		SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													
FROM	TO					Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %
366.0	371.0	71338	5.0	.0	2DA	3.13	.16	1.58	3.25	29.00		.07	6	4	10	.25		.08	
371.0	376.0	71339	5.0	.0	2DA	2.94	.13	2.86	3.56	53.40		.07	6	4	10	.32		.08	
376.0	381.0	71340	5.0	.0	2DA	2.78	.05	3.36	1.29	73.20		.07	6	4	10	.30		.08	

DDH: 67-08 UTM-N: 8342.2 UTM-E: 15602.2 UTM-ELEV: 4164.0 TOTAL DEPTH: 806.0 SECTION: 128
RFE: S2 RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %
630.0	635.0	71351	5.0	.0	2C7	3.54	.31	.07	.43	9.90			8	9	18	.09		.02		
635.0	640.0	71352	5.0	.0	2C7	3.81	.37	.55	1.15	14.20			3	23	26	.08		.04		
640.0	645.0	71353	5.0	.0	2CE	3.72	.21	.54	2.50	6.60			3	23	26	.06		.04		
645.0	650.0	71354	5.0	.0	2CE	3.87	.14	.80	1.22	5.60			3	23	26	.02		.04		
650.0	655.0	71355	5.0	.0	2D3	4.23	.01	1.99	3.04	6.60	.07		3	23	26	.16		.04		
655.0	660.0	71356	5.0	.0	2C3	3.75	.16	.48	1.52	5.10	.07	4	17	22	.05		.03			
660.0	665.0	71357	5.0	.0	2D3	3.67	.11	2.01	4.93	13.20	.07	4	17	22	.19		.03			
665.0	670.0	71358	5.0	.0	2D43	3.62	.04	4.29	12.25	17.20	.07	4	17	22	.11		.03			
670.0	675.0	71359	5.0	.0	2D43	3.65	.11	5.20	15.50	26.70	.07	4	17	22	.11		.03			
675.0	680.0	71360	5.0	.0	2D0	3.08	.13	1.47	2.59	20.20	.14	4	3	8	.24		.05			
680.0	685.0	71361	5.0	.0	2B4	3.05	.06	8.74	5.11	109.20	.96	4	3	8	.20		.05			
685.0	690.0	71362	5.0	.0	2B4	2.89	.07	2.37	3.27	48.70	.14	4	3	8	.15		.05			
690.0	695.0	71363	5.0	.0	2B/1D	2.94	.02	1.38	4.78	32.50	.07	4	3	8	.13		.05			

DDH: 67-09 UTM-N: 8740.0 UTM-E: 15199.0 UTM-ELEV: 4186.0 TOTAL DEPTH: 800.0 SECTION: 124
RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS----				-----ASSAYS-----																
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
655.0	660.0	71374	5.0	.0 2C0	3.33	.07	1.23	2.25	10.40		.01	3	22	26	.24		.13			
660.0	665.0	71375	5.0	.0 2CE	4.02	.27	.04	.88	12.30			3	22	26	.05		.13			
665.0	670.0	71376	5.0	.0 2CE	3.87	.47	.05	.50	9.20			3	22	26	.02		.13			
670.0	675.0	71377	5.0	.0 2CE	4.16	.47	.20	1.81	9.70			3	22	26	.01		.13			
675.0	680.0	71378	5.0	.0 2CE	4.18	.20	1.83	1.91	6.80		.01	7	26	33	.01		.15			
680.0	685.0	71379	5.0	.0 2E0	4.35	.25	.60	1.49	8.30			7	26	33	.02		.15			
685.0	690.0	71380	5.0	.0 2E0	4.20	.22	.83	2.49	6.30		.01	7	26	33	.02		.15			
690.0	695.0	71381	5.0	.0 2D7	3.91	.25	1.30	3.84	16.10		.01	7	26	33	.03		.15			
695.0	700.0	71382	5.0	.0 2B4	3.29	.08	4.23	9.38	38.50		.14	3	4	8	.21		.06			
700.0	705.0	71383	5.0	.0 2B4	2.86	.07	1.90	4.01	31.70			3	4	8	.44		.06			
705.0	710.0	71384	5.0	.0 2B4	2.88	.10	1.40	3.40	30.20			3	4	8	.59		.06			
710.0	715.0	71385	5.0	.0 2B4	2.83	.09	1.55	3.09	30.60			3	4	8	.68		.06			
715.0	720.0	71386	5.0	.0 2B4	2.89	.14	1.60	2.83	31.40		.01	3	3	6	.36		.07			
720.0	725.0	71387	5.0	.0 2B0	2.84	.09	.66	1.34	18.60			3	3	6	.23		.07			

DDH: 67-10 UTM-N: 8340.0 UTM-E: 15203.0 UTM-ELEV: 4103.0 TOTAL DEPTH: 741.0 SECTION: 126
 RFE: S2 RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
404.0	409.0	71394	5.0	.0	2C5	3.24	.17	.18	.65	6.10				5 14	19	.13		.04			
409.0	414.0	71395	5.0	.0	2C5	3.45	.10	.20	.61	6.90				5 14	19	.06		.04			
414.0	419.0	71396	5.0	.0	2C5	3.25	.14	.25	.44	7.10				3 16	19	.09		.05			
419.0	424.0	71397	5.0	.0	2C5	3.43	.07	.23	1.02	5.10				3 16	19	.05		.05			
424.0	429.0	71398	5.0	.0	2C0	3.35	.08	.14	1.31	5.90				3 16	19	.05		.05			
429.0	434.0	71399	5.0	.0	2C5	3.12	.17	.10	.81	5.90				3 16	19	.14		.05			
434.0	439.0	71400	5.0	.0	2C5	3.07	.24	3.06	.33	102.80		14.90	3 4	7		.25		.07			
479.0	484.0	71402	5.0	.0	2C0	3.24	.12	2.09	.80	33.90		.14	8 12	21		1.28		.10			
484.0	489.0	71403	5.0	.0	2C0	3.42	.14	2.42	1.66	44.50			8 12	21		2.35		.10			
489.0	494.0	71404	5.0	.0	2H4	3.52	.25	6.77	3.98	133.50			5 26	31		2.48		.11			
494.0	499.0	71405	5.0	.0	1D4/9	4.06	.23	1.51	1.06	28.90		.27	5 26	31		.20		.11			
499.0	506.5	71406	7.5	.0	2E0	4.26	.11	.98	.96	12.30			5 26	31		.09		.11			
506.5	514.0	71407	7.5	.0	2CE	4.29	.04	.78	.36	9.50			5 26	31		.07		.11			
514.0	519.0	71408	5.0	.0	2CE	4.52	.15	.50	.50	9.00			2 30	32		.02		.02			
519.0	524.0	71409	5.0	.0	2C0	4.24	.02	.24	.14	5.90			2 30	32		.02		.02			
524.0	529.0	71410	5.0	.0	2C0	3.29	.08	.67	.04	31.00			2 30	32		.03		.02			
529.0	534.0	71411	5.0	.0	2C0	3.71	.02	1.17	.32	23.90			2 30	32		.04		.02			
534.0	539.0	71412	5.0	.0	2CF	4.05	.35	2.86	4.30	37.20		.14	5 33	39		.02		.15			
539.0	544.0	71413	5.0	.0	2CE	4.28	.09	1.04	.96	13.50		.41	5 33	39		.03		.15			
544.0	549.0	71414	5.0	.0	2E4	4.37	.20	1.76	2.69	24.80		.01	5 33	39		.03		.15			
549.0	554.0	71415	5.0	.0	2E4	4.50	.26	2.79	3.64	31.30		.01	5 33	39		.02		.15			
554.0	559.0	71416	5.0	.0	2E0	4.42	.08	1.30	1.24	18.10		.07	1 36	38		.02		.04			
559.0	564.0	71417	5.0	.0	2E4	4.80	.11	4.63	3.60	41.40		.01	1 36	38		.02		.04			
564.0	569.0	71418	5.0	.0	1D4	4.53	.08	1.10	1.75	18.30		.21	1 36	38		.05		.04			
569.0	574.0	71419	5.0	.0	2D0	4.28	.17	2.63	2.60	23.00		.01	1 36	38		.07		.04			
574.0	579.0	71420	5.0	.0	2C0	4.18	.39	.60	1.11	9.70		.07	5 30	35		.02		.21			
579.0	584.0	71421	5.0	.0	2CF	4.10	.11	3.26	6.70	25.00		.14	5 30	35		.09		.21			
584.0	589.0	71422	5.0	.0	2E84	4.66	.41	1.50	2.66	18.30		.07	5 30	35		.02		.21			
589.0	594.0	71423	5.0	.0	2E84	4.07	.25	1.32	2.88	11.00		.01	5 30	35		.02		.21			
594.0	599.0	71424	5.0	.0	2E84	4.33	.28	2.33	3.85	13.40		.01	4 30	34		.03		.14			
599.0	604.0	71425	5.0	.0	2C0	3.85	.15	.18	.58	5.30		.14	4 30	34		.07		.14			
604.0	609.0	71426	5.0	.0	2D0	4.29	.25	1.60	4.61	9.20		.01	4 30	34		.04		.14			
609.0	614.0	71427	5.0	.0	2F4	4.83	.03	6.07	10.94	27.20		.07	4 30	34		.02		.14			
614.0	619.0	71428	5.0	.0	2F4	4.21	.10	3.95	8.04	19.40		.07	4 18	23		.10		.05			
619.0	624.0	71429	5.0	.0	2D54	3.95	.04	1.40	4.76	10.00		.07	4 18	23		.08		.05			
624.0	629.0	71430	5.0	.0	2D4	3.80	.07	4.55	12.71	26.00		.06	4 18	23		.11		.05			
629.0	634.0	71431	5.0	.0	2D4	3.34	.11	5.18	11.33	52.50		.12	4 18	23		.12		.05			
634.0	639.0	71432	5.0	.0	1D4	2.99	.18	1.29	2.48	33.20		.12	4 18	23		.13		.05			

DDH: 67-11 UTM-N: 8343.0 UTM-E: 14808.0 UTM-ELEV: 4057.0 TOTAL DEPTH: 723.0 SECTION: 124
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
487.0	492.0	71440	5.0	.0	2C0	3.56	.16	3.29	.28	58.00			12	12	25	.50		.26			
492.0	497.0	71441	5.0	.0	2D0	3.98	.18	3.75	6.01	53.30			12	12	25	.68		.26			
497.0	502.0	71442	5.0	.0	2BE4	3.42	.08	5.53	4.24	122.60			12	12	25	2.25		.26			
502.0	507.0	71443	5.0	.0	2E0	3.41	.17	1.78	1.38	25.10			12	12	25	.84		.26			
520.0	525.0	71445	5.0	.0	2EF	3.58	.11	4.99	4.00	90.90		.06	10	18	28	.06		.10			
525.0	530.0	71446	5.0	.0	2EF	4.13	.23	4.55	7.26	70.80		.07	10	18	28	.04		.10			
530.0	535.0	71447	5.0	.0	2E4	3.82	.11	6.97	13.29	113.20		.01	10	18	28	.06		.10			
535.0	540.0	71448	5.0	.0	2B64	3.28	.11	2.13	1.92	46.30		.03	10	18	28	11.19		.10			
540.0	545.0	71449	5.0	.0	2BE4	3.50	.06	3.23	5.70	48.80		.07	10	18	28	.03		.10			
545.0	550.0	71450	5.0	.0	2EF	4.67	.07	3.75	6.54	27.40		.03	10	18	28	.59		.10			
550.0	555.0	71451	5.0	.0	2E24	4.63	.17	3.95	6.28	32.20		.14	4	36	41	.03		.06			
555.0	560.0	71452	5.0	.0	2E24	4.72	.15	2.55	3.12	17.00			4	36	41	.30		.06			
560.0	565.0	71453	5.0	.0	2E2	4.92	.20	2.26	3.38	13.80			4	36	41	.05		.06			
565.0	570.0	71454	5.0	.0	2E2	4.61	.22	1.01	2.36	27.40		.07	4	36	41	.02		.06			
570.0	575.0	71455	5.0	.0	2C7	4.30	.29	1.33	1.81	19.10		.14	15	27	42	.04		.13			
575.0	580.0	71456	5.0	.0	2C7	3.99	.33	.60	.39	12.60		.01	15	27	42	.07		.13			
580.0	585.0	71457	5.0	.0	2C7	4.30	.30	.66	.56	11.10		.14	15	27	42	.02		.13			
585.0	590.0	71458	5.0	.0	2D7	4.45	.05	1.75	7.00	18.30		.07	15	27	42	.03		.13			
590.0	595.0	71459	5.0	.0	2F2	4.45	.05	1.75	7.00	18.30		.07	15	27	42	.03		.13			
595.0	600.0	71460	5.0	.0	2FH4	4.09	.15	1.36	6.23	19.70		.34	5	28	33	.06		.07			
600.0	605.0	71461	5.0	.0	2F0	3.75	.07	5.99	8.44	74.00			5	28	33	.13		.07			
605.0	610.0	71462	5.0	.0	2E4	4.63	.02	3.11	6.33	23.40		.07	5	28	33	.04		.07			
610.0	615.0	71463	5.0	.0	2E4	4.25	.02	3.38	4.72	18.40		.01	5	28	33	.02		.07			
615.0	620.0	71464	5.0	.0	2E4	4.46	.20	3.16	4.81	18.00		.01	6	18	24	.02		.03			
620.0	625.0	71465	5.0	.0	2D0	3.36	.27	2.85	4.88	20.70		.14	6	18	25	.17		.03			
625.0	630.0	71466	5.0	.0	2D0	2.95	.08	2.39	7.14	35.70			6	18	25	22.00		.03			
630.0	635.0	71467	5.0	.0	2A34	2.96	.12	1.49	3.86	30.90			6	18	24	19.00		.03			
635.0	640.0	71468	5.0	.0	2A34	2.69	.02	1.38	3.84	20.80			4	3	7	.21		.03			
640.0	645.0	71469	5.0	.0	2A0	2.90	.07	.56	1.22	11.20			2	2	4	.18		.02			
645.0	649.0	71470	4.0	.0	2A0	2.70	.07	.59	1.62	13.60			2	2	4	.15		.02			
649.0	653.0	71471	4.0	.0	2A4	2.75	.05	.85	3.85	20.40		.06	3	2	5	.13		.03			
653.0	657.0	71472	4.0	.0	2A4	2.90	.06	1.02	4.33	25.60		.27	3	2	5	.13		.03			
657.0	662.0	71473	5.0	.0	2A3	2.96	.09	.74	1.25	11.00			3	2	5	.15		.03			

DDH: 67-12 UTM-N: 8538.0 UTM-E: 14602.0 UTM-ELEV: 4061.0 TOTAL DEPTH: 1006.0 SECTION: 122+020
RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULF	-----ASSAYS-----													
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %
493.0	499.0	71481	6.0	.0	2C00	3.58	.17	.89	2.88	10.80			6	15	21	.09		.16		
499.0	505.0	71482	6.0	.0	2F40	4.64	.11	6.84	6.00	64.90			6	15	21	1.05		.16		
505.0	510.0	71483	5.0	.0	2B01	2.69	.02	.94	1.23	11.60			6	15	21	2.57		.16		
510.0	515.0	71484	5.0	.0	2B01	2.89	.04	1.89	2.09	33.00			5	8	13	4.31		.21		
515.0	520.0	71485	5.0	.0	2B01	2.68	.03	.70	1.07	14.30			5	8	13	3.82		.21		
520.0	525.0	71486	5.0	.0	2B40	3.25	.06	2.68	2.86	46.30			5	8	13	4.39		.21		
525.0	530.0	71487	5.0	.0	2H49	4.20	.20	7.04	6.20	114.80			5	8	13	3.61		.21		
530.0	535.0	71488	5.0	.0	2D00	3.46	.14	4.94	7.92	84.90			3	7	10	4.98		.14		
535.0	540.0	71489	5.0	.0	2B40	2.83	.05	1.47	3.82	28.10			3	7	10	.65		.14		
540.0	545.0	71490	5.0	.0	2A00	2.76	.06	1.21	2.02	26.90			3	7	10	.90		.14		
545.0	550.0	71491	5.0	.0	2A00	2.72	.02	1.03	2.81	27.80			3	7	10	1.02		.14		
550.0	555.0	71492	5.0	.0	2B0	2.80	.08	1.00	1.97	22.40			6	2	8	.75		.09		
555.0	560.0	71493	5.0	.0	2B0	2.80	.05	.84	1.87	16.80			6	2	8	.57		.09		
560.0	565.0	71494	5.0	.0	2D00	2.92	.04	1.91	4.01	29.10			6	2	8	.31		.09		
565.0	570.0	71495	5.0	.0	2D00	2.99	.02	1.58	3.48	26.00			6	2	8	.06		.09		
570.0	575.0	71496	5.0	.0	2D00	2.91	.03	1.60	3.37	24.30			6	9	16	.17		.12		
575.0	580.0	71497	5.0	.0	2D00	2.79	.05	3.10	5.10	49.20			6	9	16	.19		.12		
580.0	585.0	71498	5.0	.0	2D00	2.85	.08	1.38	6.63	21.80			6	9	16	.09		.12		
585.0	590.0	71499	5.0	.0	2E29	4.25	.41	4.31	5.14	58.40			6	9	16	.04		.12		
590.0	595.0	71500	5.0	.0	2E20	4.74	.09	1.38	2.22	38.00			7	26	34	.02		.15		
595.0	600.0	71501	5.0	.0	2E13	4.59	.17	3.23	4.98	46.80			7	26	34	.02		.15		
600.0	605.0	71502	5.0	.0	2E70	4.49	.08	3.93	6.02	44.80			7	26	34	.05		.15		
605.0	610.0	71503	5.0	.0	2D4	3.73	.13	4.21	9.35	43.70			7	26	34	.10		.15		
610.0	615.0	71504	5.0	.0	2E90	4.55	.21	1.63	1.67	20.10			7	29	36	.02		.20		
615.0	620.0	71505	5.0	.0	2F49	4.62	.30	6.33	10.85	73.70			7	29	36	.02		.20		
620.0	625.0	71506	5.0	.0	2E40	4.54	.15	3.68	5.65	37.50			7	29	36	.05		.20		
625.0	630.0	71507	5.0	.0	2F90	4.49	.22	2.42	2.66	29.80			7	29	36	.25		.20		
630.0	635.0	71508	5.0	.0	2E47	4.43	.17	2.32	2.54	34.50			7	30	38	.03		.16		
635.0	640.0	71509	5.0	.0	2E48	4.40	.56	3.59	3.35	55.90			7	30	38	.27		.16		
640.0	645.0	71510	5.0	.0	2E49	4.60	.65	5.16	6.39	40.60			7	30	38	.02		.16		
645.0	650.0	71511	5.0	.0	2E49	4.96	.27	2.53	4.76	24.90			7	30	38	.02		.16		
650.0	655.0	71512	5.0	.0	2H49	4.12	.53	3.14	5.42	46.00			6	13	20	.07		.07		
655.0	660.0	71513	5.0	.0	2B49	3.15	.25	1.50	5.06	37.50			6	13	20	.22		.07		
660.0	665.0	71514	5.0	.0	2B0	2.70	.06	.90	2.54	25.10			6	13	20	.21		.07		

DDH: 67-30 UTM-N: 9162.6 UTM-E: 14623.6 UTM-ELEV: 4023.7 TOTAL DEPTH: 661.0 SECTION: 124
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	ASSAYS													
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %
482.8	486.0	71524	3.2	.0	2D3	3.28	.37	5.76	.17	95.10		1.23	4	12	17	.04		.04		
486.0	489.7	71525	3.7	.0	2C3	3.33	.09	.76	1.54	9.40		.34	4	12	17	.03		.04		
489.7	494.0	71526	4.3	.0	2D4	3.26	.21	3.20	8.87	25.30		.69	4	12	17	.06		.04		
494.0	498.7	71527	4.7	.0	2D4	3.38	.19	5.43	8.64	42.60		.27	9	8	18	.05		.20		
498.7	500.0	71528	1.3	.0	2E4	4.88	.05	7.79	6.77	99.20		.14	9	8	18	.04		.20		
500.0	505.0	71529	5.0	.0	2H6	4.37	.25	5.17	4.69	83.40		.07	9	8	18	7.35		.20		
505.0	510.0	71530	5.0	.0	1D49	3.16	.14	3.54	3.66	58.00		.01	9	8	18	2.14		.20		
510.0	514.0	71531	4.0	.0	1D4	2.86	.04	.91	1.53	13.00		.01	9	8	18	2.63		.20		
514.0	517.0	71532	3.0	.0	2A4	3.09	.07	2.20	2.37	30.30		.01	11	13	25	5.98		.33		
517.0	520.0	71533	3.0	.0	2CA	2.83	.04	.69	1.20	11.50		.07	11	13	25	4.94		.33		
520.0	523.6	71534	3.6	.0	2H14	3.75	.20	6.33	6.03	101.10		.07	11	13	25	1.61		.33		
523.6	525.0	71535	1.4	.0	2F64	4.51	.21	5.64	4.90	96.80		.07	11	13	25	5.51		.33		
525.0	529.0	71536	4.0	.0	2H64	4.47	.31	6.43	6.05	96.30		.14	11	13	25	6.47		.33		
529.0	534.0	71537	5.0	.0	2F64	4.59	.12	5.94	5.62	84.70		.21	11	13	25	5.71		.33		
534.0	538.0	71538	4.0	.0	2EH4	4.53	.41	5.01	5.49	71.00		.14	13	10	24	.80		.16		
538.0	540.0	71539	2.0	.0	2H64	3.34	.36	2.38	3.60	33.90		.01	13	10	24	.27		.16		
540.0	545.0	71540	5.0	.0	2H14	4.41	.43	4.86	8.31	57.90		.07	13	10	24	.05		.16		
545.0	550.0	71541	5.0	.0	2D0	3.14	.10	5.78	1.82	113.80		1.10	13	10	24	.12		.16		
550.0	554.0	71542	4.0	.0	2D0	3.10	.07	5.90	1.86	111.90		.07	13	10	24	.20		.16		
554.0	558.0	71543	4.0	.0	2C0	2.92	.08	1.13	2.57	23.40		.01	4	4	9	.25		.05		
558.0	563.0	71544	5.0	.0	2D0	3.01	.11	2.29	4.19	44.30		.07	4	4	9	.42		.05		
563.0	568.0	71545	5.0	.0	2D0	3.12	.23	1.66	5.18	29.00		.07	4	4	9	.28		.05		
568.0	573.0	71546	5.0	.0	2C0	2.87	.08	.73	2.40	12.90			4	4	9	.26		.05		
573.0	578.0	71547	5.0	.0	2C0	2.77	.03	.79	1.87	6.90		.01	3	3	7	.52		.06		
578.0	583.0	71548	5.0	.0	2CA	2.79	.04	.70	1.31	9.70		.07	3	3	7	.36		.06		
583.0	588.0	71549	5.0	.0	2A0	2.94	.06	.84	2.09	12.70		.07	3	3	7	.22		.06		
588.0	593.0	71550	5.0	.0	2A0	2.94	.07	.66	1.53	10.50			3	3	7	.21		.06		
593.0	595.0	71551	2.0	.0	2A0	2.83	.03	.28	.55	4.10			3	3	7	.24		.06		

DDH: 70-12 UTM-N: 8200.3 UTM-E: 14209.7 UTM-ELEV: 4006.7 TOTAL DEPTH: 701.0 SECTION: 122+020
RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

							-----ASSAYS-----														
----DEPTHS----		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu	Pb	Zn	Ag(AA)	Ag(FA)	Au(FA)	Po	Py	TOT	BaO	Hg	Mn	As	Ba	S.G.
FROM	TO						%	%	%	g/mT	g/mT	g/mT	%	%	Fe	%	%	%	%	%	%
541.0	546.0	71560	5.0	.0	2A0	2.95	.08	1.61	2.52	35.30				7	5	13	.28				.10
546.0	550.0	71561	4.0	.0	2A0	2.96	.11	.76	1.06	12.60				7	5	13	.24				.10
550.0	554.5	71562	4.5	.0	2A0	2.96	.07	.67	1.25	11.20				7	5	13	.30				.10
554.5	558.5	71563	4.0	.0	1D40	3.17	.09	2.38	5.61	20.00				7	5	13	.22				.10
558.5	563.0	71564	4.5	.0	2F4	4.61	.07	7.52	11.65	76.70				5	30	36	.05				.08
563.0	566.8	71565	3.8	.0	2F4	4.89	.16	6.64	9.00	59.10				5	30	36	.06				.08
566.8	567.3	71566	.5	.0	2H43	4.60	.49	4.70	6.20	70.00				5	30	36	.03				.08
567.3	570.9	71567	3.6	.0	2E4	4.71	.14	6.48	8.64	55.30				5	30	36	.14				.08
570.9	572.8	71568	1.9	.0	2F4	4.84	.09	6.26	11.06	66.50				5	30	36	.03				.08
572.8	576.0	71569	3.2	.0	2E49	4.99	.39	3.66	6.11	46.30				5	30	36	.03				.08
576.0	581.0	71570	5.0	.0	2F4	4.88	.15	7.31	7.36	66.20				4	26	31	.04				.06
581.0	586.0	71571	5.0	.0	2F4	4.99	.12	7.98	11.40	73.40				4	26	31	.04				.06
586.0	591.0	71572	5.0	.0	2E4	4.75	.15	4.14	7.10	31.10				4	26	31	.03				.06
591.0	596.0	71573	5.0	.0	2A0	2.90	.14	.86	1.97	22.70				4	26	31	.40				.06
596.0	601.0	71574	5.0	.0	2A9	3.03	.54	1.63	2.15	50.70				6	5	12	.25				.10
601.0	604.0	71575	3.0	.0	2A0	2.89	.18	.39	1.14	17.20				6	5	12	.58				.10

DDH: 70-13 UTM-N: 7561.2 UTM-E: 14814.0 UTM-ELEV: 4011.2 TOTAL DEPTH: 706.0 SECTION:
RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
400.0	463.5	71582	63.5	.0	****	2.75															
463.5	467.0	71583	3.5	.0	2B0	2.79	.01	.03	.14	1.50			6	13	19	.31		.15			
467.0	471.0	71584	4.0	.0	2B0	3.32	.25	.88	1.72	13.20			6	13	19	.11		.15			
471.0	475.0	71585	4.0	.0	2D4	3.49	.10	3.28	8.82	25.20			6	13	19	.06		.15			
475.0	479.0	71586	4.0	.0	2G0	4.66	.12	6.46	7.34	81.20			6	13	19	.10		.15			
479.0	483.0	71587	4.0	.0	2A0	2.84	.04	.76	1.72	16.30			6	13	19	.73		.15			
483.0	488.0	71588	5.0	.0	2A0	2.81	.06	.90	2.28	18.20			3	3	7	.45		.05			
488.0	493.0	71589	5.0	.0	2A0	2.84	.05	.39	.64	9.60			3	3	7	.45		.05			
493.0	498.0	71590	5.0	.0	2A0	2.70	.04	.68	1.08	14.60			3	3	7	.60		.05			
498.0	503.0	71591	5.0	.0	2A0	2.72	.04	.51	.82	13.60			3	3	7	.51		.05			
528.0	531.5	71593	3.5	.0	2B4	2.98	.03	6.71	5.15	180.00			3	1	5	.04		.07			
531.5	535.0	71594	3.5	.0	2B0	2.89	.05	5.38	.39	115.50			3	1	5	.14		.07			

```
DDH: 70-17      UTM-N: 3596.0    UTM-E: 14209.3    UTM-ELEV: 4019.0    TOTAL DEPTH: 703.0    SECTION: 120+000
RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0      0 DHD CALC: 1 SS CALC: 1
```

[illegible]

DDH: 71-01 UTM-N: 9118.0 UTM-E: 13975.0 UTM-ELEV: 3967.2 TOTAL DEPTH: 695.0 SECTION: 121+000
RFE: 52 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

-----DEPTHS-----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
614.0	615.5	71622	1.5	.0	2A0	2.90	.06	.83	2.50	14.60			4	4	9	.14		.04			
615.5	616.5	71623	1.0	.0	2H0	3.79	.26	2.93	6.24	58.40			4	4	9	.17		.04			
616.5	620.0	71624	3.5	.0	2A4	2.94	.08	2.40	1.77	47.90			4	4	9	.17		.04			
620.0	625.0	71625	5.0	.0	2A4	2.93	.09	1.78	3.60	39.80			4	4	9	.20		.04			
625.0	630.0	71626	5.0	.0	2A0	2.75	.04	.78	1.75	16.10			4	4	9	.13		.04			

DDH: 71-02 UTM-N: 8600.0 UTM-E: 13793.0 UTM-ELEV: 4005.0 TOTAL DEPTH: 603.0 SECTION: 118+000
RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

PAGE : 54

[illegible]

PAGE: 55

[illegible]

DDH: 71-05 UTM-N: 7721.0 UTM-E: 14596.0 UTM-ELEV: 4001.5 TOTAL DEPTH: 567.0 SECTION: 126
RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS----						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
514.0	517.5	71683	3.5	.0	2A0	3.04	.32	1.79	.55	69.30				5	18	23	.14		.21		
517.5	522.5	71684	5.0	.0	2F4	4.05	.18	5.75	6.11	71.60			.27	5	18	23	.64		.21		
522.5	527.5	71685	5.0	.0	2F4	4.61	.18	5.18	5.49	83.60			.27	5	18	23	6.80		.21		
527.5	533.0	71686	5.5	.0	2D0	2.99	.17	2.46	4.08	57.10			.62	5	18	23	1.29		.21		
533.0	536.0	71687	3.0	.0	2DE	3.66	.15	3.98	4.86	76.30			.14	5	7	12	.08		.09		
536.0	540.0	71688	4.0	.0	2D0	2.94	.18	2.56	5.27	36.80			.27	5	7	12	.75		.09		
540.0	544.0	71689	4.0	.0	2D0	3.04	.15	2.06	6.03	39.30			.21	5	7	12	.69		.09		
544.0	549.0	71690	5.0	.0	2A4	2.94	.07	1.83	3.53	36.80			.14	5	7	12	.20		.09		
549.0	555.0	71691	6.0	.0	2A4	2.90	.08	1.67	4.22	34.40			.21	3	3	6	.24		.04		
555.0	560.0	71692	5.0	.0	2A4	2.89	.11	3.54	4.48	60.70			.27	3	3	6	.22		.04		
560.0	565.0	71693	5.0	.0	2A0	2.69	.08	.89	3.09	26.30			.27	3	3	6	.26		.04		

DDH: 72-12 UTM-N: 7366.7 UTM-E: 15116.5 UTM-ELEV: 4018.0 TOTAL DEPTH: 393.0 SECTION: 131
RFE: 92 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
320.9	324.5	71835	3.6	.0	2D3	3.30	.08	1.85	3.40	29.60				11	10	22	.73		.24		
324.5	332.0	71836	7.5	.0	****	2.83	.08	.23	.35	6.80				3	3	6	.53		.25		
332.0	334.5	71837	2.5	.0	****	2.68	.06	.33	.73	9.40				4	4	9	.16		.33		

DDH: 72-15 UTM-N: 8569.9 UTM-E: 15442.6 UTM-ELEV: 4188.3 TOTAL DEPTH: 700.0 SECTION: 126
RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----		-----ASSAYS-----																		
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
611.0	616.0	71870	5.0	.0 2D7	3.42	.10	1.48	4.88	10.50		.07	8	16	25	.04		.03			
616.0	621.0	71871	5.0	.0 2D0	3.39	.06	1.02	3.05	7.60		.14	8	16	25	.06		.03			
621.0	626.0	71872	5.0	.0 2D4	4.08	.05	3.97	9.03	20.50		.21	4	14	19	.10		.03			
626.0	631.0	71873	5.0	.0 2D4	3.57	.09	3.14	7.86	22.70		.21	4	14	19	.11		.03			
631.0	636.0	71874	5.0	.0 2D0	3.25	.16	2.98	5.72	37.10		.07	4	14	19	.21		.03			
636.0	641.0	71875	5.0	.0 2B4	2.96	.08	1.18	3.49	14.90		.21	4	14	19	.30		.03			
641.0	646.0	71876	5.0	.0 2B0	2.94	.11	1.52	2.58	23.80		.01	4	14	19	.39		.03			

DDH: 72-16 UTM-N: 8978.1 UTM-E: 15011.7 UTM-ELEV: 4161.8 TOTAL DEPTH: 810.0 SECTION: 122+020
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

-----DEPTHS-----					-----ASSAYS-----																	
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.	
567.0	572.0	71884	5.0	.0	2D37	4.06	.11	5.10	7.08	40.10			1	26	27	10.40						.06
572.0	577.0	71885	5.0	.0	2C4	4.67	.08	5.98	6.47	67.10			1	26	27	10.42						.06
577.0	582.0	71886	5.0	.0	2E41	3.96	.03	1.62	3.02	22.90			1	26	27	3.05						.06
582.0	587.0	71887	5.0	.0	2C3	3.67	.01	.08	.10	4.90			1	26	27	.01						.06
587.0	592.0	71888	5.0	.0	2C3	3.59	.02	.14	.10	5.60			1	26	27	.05						.06
592.0	597.0	71889	5.0	.0	2E1	4.17	.03	.56	.33	7.60			4	26	31	.05						.04
597.0	602.0	71890	5.0	.0	2F41	4.30	.02	3.28	7.53	30.40			4	26	31	.06						.04
602.0	607.0	71891	5.0	.0	2D48	3.76	.03	4.77	13.30	66.00			4	26	31	.10						.04
607.0	612.0	71892	5.0	.0	2G41	4.15	.15	3.67	5.91	42.50			4	26	31	2.32						.04
612.0	617.0	71893	5.0	.0	2E01	4.69	.11	1.88	3.46	15.10			1	32	34	.07						.02
617.0	622.0	71894	5.0	.0	2E01	4.81	.23	.04	.10	5.90			1	32	34	.04						.02
622.0	627.0	71895	5.0	.0	2E01	4.97	.19	.06	.14	7.00			1	32	34	.06						.02
627.0	632.0	71896	5.0	.0	2D41	3.17	.09	2.80	9.50	23.10			1	32	34	.25						.02
632.0	637.0	71897	5.0	.0	2C01	3.15	.11	1.28	3.10	13.80			1	25	27	.26						.02
637.0	642.0	71898	5.0	.0	2E4	3.99	.21	2.27	3.65	17.10			1	25	27	.15						.02
642.0	647.0	71899	5.0	.0	2E18	3.83	.09	.64	1.92	12.60			1	25	27	.16						.02
647.0	652.0	71900	5.0	.0	2E18	3.66	.10	1.76	1.59	15.40			1	25	27	.09						.02
652.0	657.0	71901	5.0	.0	2E41	3.84	.14	2.89	1.80	17.20			3	28	31	.07						.17
657.0	662.0	71902	5.0	.0	2C31	3.50	.05	.34	1.41	6.80			3	28	31	.10						.17
662.0	667.0	71903	5.0	.0	2E81	4.14	.20	.66	1.34	8.80			3	28	31	.05						.17
667.0	672.0	71904	5.0	.0	2E89	4.30	.31	1.06	1.88	11.70			3	28	31	.15						.17
672.0	677.0	71905	5.0	.0	2E89	3.91	.30	.56	1.26	8.80			3	29	32	.04						.13
677.0	682.0	71906	5.0	.0	2C9	3.59	.50	.12	.58	9.40			3	29	32	.04						.13
682.0	687.0	71907	5.0	.0	2E8	3.83	.19	.24	.99	5.60			3	29	32	.04						.13
687.0	692.0	71908	5.0	.0	2E11	4.42	.11	.08	.72	5.50			3	29	32	.05						.13
692.0	697.0	71909	5.0	.0	2C0	3.52	.17	.84	2.88	8.10			3	18	22	.10						.03
697.0	702.0	71910	5.0	.0	2C0	3.26	.12	.76	1.72	8.50			3	18	22	.13						.03
702.0	707.0	71911	5.0	.0	2D0	3.41	.10	1.18	3.05	7.50			3	18	22	.17						.03
707.0	712.0	71912	5.0	.0	2C0	3.52	.10	.18	1.12	4.20			3	18	22	.10						.03
712.0	717.0	71913	5.0	.0	2C0	3.71	.17	.12	.87	4.40			6	23	29	.04						.22
717.0	722.0	71914	5.0	.0	2C9	3.52	.74	.22	1.18	14.60			6	23	29	.05						.22
722.0	727.0	71915	5.0	.0	2E89	3.66	1.00	.60	.58	16.00			6	23	29	.03						.22
727.0	732.0	71916	5.0	.0	2E89	3.73	1.50	.18	.50	12.00			6	23	29	.03						.22
732.0	737.0	71917	5.0	.0	2E89	3.66	1.50	.26	.45	12.60			7	24	32	.02						.17
737.0	742.0	71918	5.0	.0	2E89	3.96	.73	.12	.42	7.50			7	24	32	.03						.17
742.0	747.0	71919	5.0	.0	2E89	3.96	.75	.30	1.41	8.40			7	24	32	.02						.17
747.0	752.0	71920	5.0	.0	2E89	3.87	.49	.50	.80	6.90			7	24	32	.03						.17
752.0	757.0	71921	5.0	.0	2E89	3.98	.60	1.62	1.61	12.60			4	28	33	.02						.13
757.0	762.0	71922	5.0	.0	2E81	4.28	.30	.28	1.65	5.50			4	28	33	.01						.13
762.0	767.0	71923	5.0	.0	2E81	4.05	.26	.74	2.07	5.60			4	28	33	.02						.13
767.0	772.0	71924	5.0	.0	2D39	3.97	.06	1.76	7.12	6.60			4	28	33	.08						.13
772.0	777.0	71925	5.0	.0	2C3	3.88	.04	.44	1.70	3.90			4	16	20	.04						.04
777.0	782.0	71926	5.0	.0	2D3	3.87	.05	3.90	8.82	19.90			4	16	20	.09						.04
782.0	787.0	71927	5.0	.0	2Q9?	3.15	.14	1.97	5.94	20.00			4	16	20	.22						.04
787.0	792.0	71928	5.0	.0	1D41	2.79	.05	.32	1.08	10.80			4	16	20	.30						.04

DDH: 72004 UTM-N: 8801.1 UTM-E: 13597.3 UTM-ELEV: 4036.2 TOTAL DEPTH: 600.0 SECTION:
RFE: RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
509.0	511.5	71701	2.5	.0	2J4	3.79	.13	5.04	11.90	77.80			4	4	9	.11		.05			
511.5	516.5	71702	5.0	.0	2C0	2.81	.05	1.69	3.67	34.00			4	4	9	.14		.05			
516.5	521.0	71703	4.5	.0	2B4	2.69	.04	1.41	4.73	24.60			4	4	9	.10		.05			
521.0	526.1	71704	5.1	.0	2B44	2.85	.06	3.53	7.73	60.90			4	4	9	.08		.05			

[illegible]

DDH: 72007 UTM-N: 9804.6 UTM-E: 13296.7 UTM-ELEV: 4040.2 TOTAL DEPTH: 437.0 SECTION:
 RFE: RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	ASSAYS														
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. U.R.
90.0	95.0	71735	5.0	.0	****	.50	.23	.60	.60												
95.0	100.0	71736	5.0	.0	****	.50	.24	5.70	6.20												
100.0	105.0	71737	5.0	.0	****	.50		3.50	5.70												
105.0	110.0	71738	5.0	.0	****	.50	.17	6.00	6.10												
110.0	115.0	71739	5.0	.0	****	.50	.01	4.30	6.10												
115.0	120.0	71740	5.0	.0	****	.50	.23	3.80	4.50												
120.0	125.0	71741	5.0	.0	****	.50	.32	5.00	7.60												
125.0	130.0	71742	5.0	.0	****	.50	.02	5.60	8.80												
130.0	135.0	71743	5.0	.0	****	.50	.12	7.60	8.00												
135.0	140.0	71744	5.0	.0	****	.50	.21	6.70	6.00												
140.0	145.0	71745	5.0	.0	****	.50	.24	4.60	5.60												
145.0	150.0	71746	5.0	.0	****	.50	.22	5.30	5.70												
150.0	155.0	71747	5.0	.0	****	.50	.13	7.00	6.50												
155.0	160.0	71748	5.0	.0	****	.50	.16	6.70	5.70												
160.0	165.0	71749	5.0	.0	****	.50	.10	6.30	7.70												
165.0	170.0	71750	5.0	.0	****	.50	.12	5.30	5.50												
170.0	175.0	71751	5.0	.0	****	.50	.18	6.60	6.30												
175.0	180.0	71752	5.0	.0	****	.50	.17	5.40	6.10												
180.0	185.0	71753	5.0	.0	****	.50	.14	5.90	6.50												
185.0	190.0	71754	5.0	.0	****	.50	.14	5.00	6.90												
190.0	195.0	71755	5.0	.0	****	4.26	.07	.81	.39	12.00			2	34	37	.23		.02			
195.0	200.0	71756	5.0	.0	****	3.83	.03	.21	.18	5.00			2	34	37	.07		.02			
200.0	205.0	71757	5.0	.0	****	4.86	.37	2.35	2.15	21.00			2	34	37	.02		.02			
205.0	210.0	71758	5.0	.0	****	4.97	.39	2.21	2.60	19.00			2	34	37	.16		.02			
210.0	215.0	71759	5.0	.0	****	4.89	.36	.87	.16	12.00			2	37	40	.03		.02			
215.0	220.0	71760	5.0	.0	****	4.33	.19	.72	.21	11.00			2	37	40	.03		.02			
220.0	225.0	71761	5.0	.0	****	4.58	.06	.88	.13	11.00			2	37	40	.02		.02			
225.0	230.0	71762	5.0	.0	****	4.38	.07	.65	.09	10.00			2	37	40	.02		.02			
230.0	235.0	71763	5.0	.0	****	4.18	.11	2.24	.12	23.00			2	35	37	.02		.02			
235.0	240.0	71764	5.0	.0	****	4.39	.04	.92	.09	11.00			2	35	37	.05		.02			
240.0	245.0	71765	5.0	.0	****	4.70	.13	2.14	2.28	23.00			2	35	37	.04		.02			
245.0	250.0	71766	5.0	.0	****	4.38	.02	.44	.47	7.00			2	35	37	.02		.02			
250.0	255.0	71767	5.0	.0	****	4.11	.04	.27	.17	5.00			2	25	28	.04		.06			
255.0	260.0	71768	5.0	.0	****	3.31	.05	.20	.12	6.00			2	25	28	.22		.06			
260.0	265.0	71769	5.0	.0	****	4.20	.18	1.35	.55	19.00			2	25	28	.54		.06			
265.0	270.0	71770	5.0	.0	****	4.55	.16	4.46	4.88	57.70			2	25	28	12.71		.06			
270.0	275.0	71771	5.0	.0	****	4.64	.24	5.00	6.15	51.10			6	28	35	19.21		.16			
275.0	280.0	71772	5.0	.0	****	4.14	.21	2.50	3.05	55.80			6	28	35	.29		.16			
280.0	285.0	71773	5.0	.0	****	4.10	.59	.38	1.82	7.90			6	28	35	.06		.16			
285.0	290.0	71774	5.0	.0	****	4.48	.55	.56	1.98	7.00			6	28	35	.03		.16			
290.0	295.0	71775	5.0	.0	****	4.48	.78	.36	1.46	7.40			7	35	42	.02		.13			
295.0	300.0	71776	5.0	.0	****	4.42	.44	1.88	2.67	9.40			7	35	42	.03		.13			
300.0	305.0	71777	5.0	.0	****	4.57	.43	.92	3.19	7.80			7	35	42	.03		.13			
305.0	310.0	71778	5.0	.0	****	4.67	.50	.78	2.90	8.10			7	35	42	.02		.13			
310.0	315.0	71779	5.0	.0	****	4.48	.20	3.00	7.42	11.80			4	36	40	.02		.09			
315.0	320.0	71780	5.0	.0	****	4.85	.05	3.81	7.96	13.50			4	36	40	.01		.09			
320.0	325.0	71781	5.0	.0	****	5.02	.08	2.07	1.60	8.60			4	36	40	.02		.09			
325.0	330.0	71782	5.0	.0	****	4.61	.30	.60	1.90	6.30			4	36	40	.11		.09			
330.0	335.0	71783	5.0	.0	****	4.24	.23	1.08	3.56	7.00			7	30	37	.08		.12			
335.0	340.0	71784	5.0	.0	****	4.15	.17	.22	2.69	4.90			7	30	37	.03		.12			
340.0	345.0	71785	5.0	.0	****	4.28	.25	.84	5.28	6.90			7	30	37	.02		.12			

DDH: 72007 UTM-N: 9804.6 UTM-E: 13996.7 UTM-ELEV: 4040.2 TOTAL DEPTH: 437.0 SECTION:
 RFE: RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

---DEPTHS---						---ASSAYS---															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
345.0	350.0	71786	5.0	.0	****	4.42	.17	4.90	9.16	16.80			7	30	37	.02		.12			
350.0	355.0	71787	5.0	.0	****	4.32	.20	2.30	2.89	8.70			7	33	41	.02		.13			
355.0	360.0	71788	5.0	.0	****	4.52	.21	.98	2.94	6.20			7	33	41	.02		.13			
360.0	365.0	71789	5.0	.0	****	4.63	.26	.74	2.79	5.00			7	33	41	.02		.13			
365.0	370.0	71790	5.0	.0	****	4.62	.27	.50	1.62	5.50			7	33	41	.03		.13			
370.0	375.0	71791	5.0	.0	****	4.78	.30	.62	1.99	6.40			3	38	41	.05		.04			
375.0	380.0	71792	5.0	.0	****	4.88	.23	1.62	3.37	8.00			3	38	41	.01		.04			
380.0	385.0	71793	5.0	.0	****	5.21	.36	3.31	4.97	14.00			3	38	41	.02		.04			
385.0	390.0	71794	5.0	.0	****	4.93	.50	2.92	5.42	16.00			3	38	41	.01		.04			
390.0	395.0	71795	5.0	.0	****	4.79	.45	2.38	5.83	15.00			3	20	24	.01		.03			
395.0	400.0	71796	5.0	.0	****	4.63	.34	2.79	7.13	17.00			3	20	24	.03		.03			
400.0	405.0	71797	5.0	.0	****	4.29	.19	4.43	6.99	42.00			3	20	24	.22		.03			
405.0	410.0	71798	5.0	.0	****	3.27	.11	2.03	5.14	22.00			3	20	24	.26		.03			
410.0	415.0	71799	5.0	.0	****	3.30	.11	2.02	3.94	19.00			5	7	12	.23		.03			
415.0	420.0	71800	5.0	.0	****	3.05	.09	3.78	7.83	28.00			5	7	12	.28		.03			
420.0	425.0	71801	5.0	.0	****	3.34	.07	7.46	15.29	71.00			5	7	12	.07		.03			
425.0	430.0	71802	5.0	.0	****	3.33	.13	3.66	11.72	34.00			5	7	12	.08		.03			
430.0	437.0	71803	7.0	.0	****	2.92	.07	.82	3.14	15.00			4	8	13	.12		.02			

[illegible]

DDH: 73-01 UTM-N: 9684.3 UTM-E: 14711.2 UTM-ELEV: 4182.6 TOTAL DEPTH: 549.0 SECTION: 117+000
RFE: 32 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

-----DEPTHS-----						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
279.0	284.0	71933	5.0	.0	2E42	3.54	.08	2.43	3.34	27.50			4	15	20	.27		.07			
284.0	289.0	71934	5.0	.0	2E42	3.96	.18	1.98	2.03	40.20			4	15	20	2.23		.07			
289.0	294.0	71935	5.0	.0	1D4	2.65	.04	.05	.06	2.60			4	15	20	.28		.07			
294.0	299.0	71936	5.0	.0	1D4	2.77	.04	.07	.08	5.40			4	1	6	.10		.06			
299.0	304.0	71937	5.0	.0	0Q90	3.13	.24	5.50	.14	210.00			4	1	6	.05		.06			
304.0	309.0	71938	5.0	.0	1D4	2.86	.13	3.99	.22	92.70			4	1	6	3.53		.06			
309.0	313.0	71939	4.0	.0	1D40	2.82	.21	1.84	1.88	55.50			4	1	6	.03		.06			
313.0	319.0	71940	6.0	.0	2G40	3.60	.11	4.57	5.89	232.00			6	8	14	13.06		.08			
319.0	324.0	71941	5.0	.0	2H40	3.79	.24	2.29	15.40	42.50			6	8	14	.36		.08			
324.0	329.0	71942	5.0	.0	2L14	2.92	.05	2.03	4.05	30.40			6	8	14	3.36		.08			

[illegible]

[illegible]

DDH: 73028 UTM-N: 9176.4 UTM-E: 13801.5 UTM-ELEV: 3948.2 TOTAL DEPTH: 330.0 SECTION:
 RFE: RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %
235.0	240.0	72001	5.0	.0	****	3.00	.19	.46	.79	9.00			9	15	25	.09		.13		
240.0	245.0	72002	5.0	.0	****	2.88	.04	2.94	3.46	22.00			9	15	25	.13		.13		
245.0	250.0	72003	5.0	.0	****	3.47	.08	2.32	4.43	31.00			9	15	25	.09		.13		
250.0	255.0	72004	5.0	.0	****	4.30	.26	4.93	7.77	58.00			9	15	25	.46		.13		
255.0	260.0	72005	5.0	.0	****	4.61	.24	5.60	8.05	67.00			9	15	25	.14		.13		
260.0	265.0	72006	5.0	.0	****	4.63	.19	6.93	8.82	77.00			7	11	18	1.65		.11		
265.0	270.0	72007	5.0	.0	****	3.23	.22	3.70	7.44	51.00			7	11	18	.26		.11		
270.0	275.0	72008	5.0	.0	****	3.23	.08	3.41	7.12	59.00			7	11	18	.28		.11		
275.0	280.0	72009	5.0	.0	****	3.03	.08	1.66	4.35	34.00			7	11	18	.24		.11		
280.0	285.0	72010	5.0	.0	****	3.01	.12	1.95	3.00	36.00			5	4	9	.24		.03		
285.0	290.0	72011	5.0	.0	****	3.03	.08	1.86	4.79	32.00			5	4	9	.29		.03		
290.0	295.0	72012	5.0	.0	****	3.13	.12	2.12	5.46	38.00			5	4	9	.18		.03		
295.0	300.0	72013	5.0	.0	****	2.69	.05	.82	1.94	20.00			5	4	9	.30		.03		
300.0	305.0	72014	5.0	.0	****	2.81	.04	1.51	2.73	28.00			2	2	5	.18		.05		
305.0	310.0	72015	5.0	.0	****	2.81	.04	.01	.04	2.00			2	2	5	.23		.05		
310.0	315.0	72016	5.0	.0	****	2.74	.05	.87	1.60	12.00			2	2	5	.20		.05		
315.0	320.0	72017	5.0	.0	****	2.92	.09	2.31	4.06	52.00			2	2	5	.29		.05		
320.0	325.0	72018	5.0	.0	****	2.83	.06	1.05	2.19	24.00			3	2	6	.35		.05		
325.0	330.0	72019	5.0	.0	****	2.81	.05	.52	1.18	9.00			3	2	6	.27		.05		

DDH: 73029 UTM-N: 9956.6 UTM-E: 14589.8 UTM-ELEV: 4120.0 TOTAL DEPTH: 307.0 SECTION:
RFE: RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

---DEPTHS---						---ASSAYS---															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
147.0	152.0	72023	5.0	.0	****	3.21	.24	1.44	2.03	40.00			7	9	16	1.00		.07			
152.0	157.0	72024	5.0	.0	****	3.66	.15	.77	2.31	24.00			4	20	24	.05		.06			
157.0	162.0	72025	5.0	.0	****	3.45	.13	.36	.91	12.00			5	16	22	.06		.06			
212.0	217.0	72028	5.0	.0	****	3.63	.41	1.95	.21	56.00			9	16	26	.10		.07			
217.0	222.0	72029	5.0	.0	****	3.31	.25	.82	.19	30.00			9	7	17	.15		.10			
222.0	227.0	72030	5.0	.0	****	3.55	.19	.15	1.31	15.00			5	18	23	.09		.06			
227.0	232.0	72031	5.0	.0	****	2.91	.03	.17	.16	10.00			3	1	5	.19		.07			
232.0	237.0	72032	5.0	.0	****	3.59	.20	.03	.40	7.00			5	19	25	.08		.05			
237.0	242.0	72033	5.0	.0	****	2.76	.16	.31	.25	10.00			5	4	10	.16		.05			
242.0	247.0	72034	5.0	.0	****	3.38	.12	1.75	3.70	24.00			6	10	17	.12		.05			
247.0	252.0	72035	5.0	.0	****	3.35	.04	1.97	4.94	22.00			2	13	15	.17		.04			
252.0	257.0	72036	5.0	.0	****	3.20	.11	1.98	3.85	24.00			3	7	11	.17		.05			
257.0	262.0	72037	5.0	.0	****	3.27	.08	4.75	6.29	66.00			3	9	12	.13		.04			
262.0	267.0	72038	5.0	.0	****	3.00	.05	.77	.34	32.00			3	5	8	.13		.06			
267.0	272.0	72039	5.0	.0	****	3.42	.05	3.72	7.41	31.00			2	12	15	.08		.03			
272.0	277.0	72040	5.0	.0	****	3.22	.18	1.12	1.32	20.00			5	10	16	.08		.03			
277.0	282.0	72041	5.0	.0	****	2.94	.18	.62	.96	13.00			5	6	12	.14		.05			
282.0	287.0	72042	5.0	.0	****	3.91	.10	3.67	12.45	32.00			4	15	20	.04		.05			
287.0	292.0	72043	5.0	.0	****	3.46	.07	6.08	9.38	49.00			4	9	14	.08		.03			
292.0	297.0	72044	5.0	.0	****	3.68	.22	2.16	8.79	24.00			9	13	22	.07		.04			
297.0	302.0	72045	5.0	.0	****	3.11	.18	2.55	4.37	41.00			7	2	9	.25		.04			
302.0	307.0	72046	5.0	.0	****	3.07	.12	1.26	2.16	29.00			5	5	11	.12		.06			

DDH: 74-01 UTM-N: 9701.5 UTM-E: 14908.2 UTM-ELEV: 4112.8 TOTAL DEPTH: 523.0 SECTION: 118+000
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
314.0	319.0	72052	5.0	.0	2D40	3.00	.10	2.97	8.85	53.80			5	11	16	.21		.13			
319.0	324.0	72053	5.0	.0	1D40	3.17	.03	.66	.68	16.50			5	11	16	.09		.13			
324.0	329.0	72054	5.0	.0	2D40	3.07	.07	6.51	3.18	73.00			4	8	13	.11		.11			
358.0	363.0	72056	5.0	.0	2C74	3.32	.37	1.92	.70	23.50			6	16	22	.10		.07			
363.0	368.0	72057	5.0	.0	2C74	3.38	.17	1.78	3.00	23.10			6	16	22	.15		.07			
368.0	373.0	72058	5.0	.0	2C30	3.82	.11	1.78	2.37	17.20			6	16	22	.08		.07			
373.0	378.0	72059	5.0	.0	2C3	3.02	.18	1.12	1.76	18.50			6	16	22	.16		.07			
391.0	396.0	72061	5.0	.0	2A40	3.21	.10	2.94	6.32	27.00			3	15	18	.11		.07			
396.0	401.0	72062	5.0	.0	2A4	3.40	.05	4.08	10.00	32.20			3	15	18	.22		.07			
401.0	406.0	72063	5.0	.0	2D34	3.30	.10	2.00	4.93	29.70			3	15	18	.13		.07			
406.0	411.0	72064	5.0	.0	2A4	3.25	.03	2.73	7.23	22.40			1	15	16	.17		.02			
411.0	416.0	72065	5.0	.0	2A4	3.18	.05	4.70	7.61	50.10			1	15	16	.16		.02			
416.0	421.0	72066	5.0	.0	2A4	3.36	.02	1.94	7.40	19.50			1	15	16	.19		.02			
421.0	426.0	72067	5.0	.0	2A4	3.35	.02	2.42	5.70	20.50			1	15	16	.15		.02			
426.0	431.0	72068	5.0	.0	2A4	3.45	.03	1.78	5.22	23.30			1	17	19	.14		.02			
431.0	436.0	72069	5.0	.0	2A4	3.29	.02	.94	3.26	16.10			1	17	19	.17		.02			
436.0	441.0	72070	5.0	.0	2A0	3.23	.03	.58	1.94	13.70			1	17	19	.16		.02			
441.0	446.0	72071	5.0	.0	2A4	3.34	.02	1.56	4.36	23.10			1	17	19	.13		.02			
446.0	451.0	72072	5.0	.0	2A0	3.08	.03	.52	.72	24.80			1	18	19	.22		.02			
451.0	456.0	72073	5.0	.0	2A0	3.23	.04	.34	1.84	9.10			1	18	19	.19		.02			
456.0	461.0	72074	5.0	.0	2A0	3.14	.06	.50	1.80	13.50			1	18	19	.18		.02			
461.0	466.0	72075	5.0	.0	2A0	3.28	.03	.38	.98	13.50			1	18	19	.14		.02			
466.0	471.0	72076	5.0	.0	2A0	3.19	.03	.54	1.82	17.20			2	22	24	.23		.03			
471.0	476.0	72077	5.0	.0	2A4	3.63	.02	2.59	6.42	19.50			2	22	24	.16		.03			
476.0	481.0	72078	5.0	.0	2F00	4.76	.01	2.28	5.61	16.30			2	22	24	.04		.03			
481.0	486.0	72079	5.0	.0	2D40	4.08	.02	5.07	10.47	37.10			2	22	24	.05		.03			
486.0	491.0	72080	5.0	.0	2D0	3.34	.06	2.35	5.70	27.70			2	22	24	.13		.03			

DDH: 74-02 UTM-N: 9032.6 UTM-E: 13965.5 UTM-ELEV: 3965.5 TOTAL DEPTH: 474.0 SECTION: 117+000
RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

-----DEPTHS----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. U.R.
272.0	277.0	72084	5.0	.0	2D0	2.97	.09	1.71	3.99	28.70			3	4	8	.21		.04			
277.0	282.0	72085	5.0	.0	2D0	2.93	.10	1.76	4.59	42.00			3	4	8	.22		.04			
282.0	287.0	72086	5.0	.0	2D0	2.93	.24	1.72	3.17	45.20			3	4	8	.23		.04			
287.0	292.0	72087	5.0	.0	2E40	3.62	.13	5.80	6.92	68.80			7	23	30	.35		.19			
292.0	297.0	72088	5.0	.0	2F4	4.29	.10	5.45	8.36	56.40			7	23	30	.07		.19			
297.0	302.0	72089	5.0	.0	2F4	4.41	.08	6.41	8.72	58.90			7	23	30	.14		.19			
302.0	307.0	72090	5.0	.0	2F40	4.33	.18	7.22	7.32	60.90			7	23	30	.89		.19			

DDH: 74-07 UTM-N: 9398.7 UTM-E: 15001.9 UTM-ELEV: 4138.5 TOTAL DEPTH: 777.0 SECTION: 120+000
 RFE: 92 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	ASSAYS														
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Pt %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
404.0	409.0	72236	5.0	.0	2D01	3.36	.10	6.99	3.73	126.50			5	9	14	.18		.10			
409.0	414.0	72237	5.0	.0	2D01	3.06	.06	3.29	3.25	35.30			5	9	14	.09		.10			
414.0	419.0	72238	5.0	.0	1D41	2.87	.08	1.46	.64	36.30			5	9	14	.12		.10			
419.0	424.0	72239	5.0	.0	2C31	3.09	.13	4.28	1.72	113.80			5	9	14	.13		.10			
424.0	429.0	72240	5.0	.0	2D45	3.43	.21	4.10	4.40	49.40			5	9	14	.11		.10			
429.0	434.0	72241	5.0	.0	2C31	3.53	.09	1.76	2.48	16.50			3	21	24	.10		.05			
434.0	439.0	72242	5.0	.0	2C31	3.35	.27	1.06	1.00	20.40			3	21	24	.07		.05			
439.0	444.0	72243	5.0	.0	2C31	3.65	.11	3.35	3.98	32.30			3	21	24	.10		.05			
444.0	449.0	72244	5.0	.0	2C3&	3.62	.11	.73	1.84	7.20			3	21	24	.03		.05			
449.0	454.0	72245	5.0	.0	2C3&	3.71	.12	1.54	2.22	12.60			3	24	28	.07		.06			
454.0	459.0	72246	5.0	.0	2C39	4.03	.21	.37	.96	6.00			3	24	28	.02		.06			
459.0	464.0	72247	5.0	.0	2C3	3.77	.07	1.02	1.86	10.30			3	24	28	.06		.06			
464.0	469.0	72248	5.0	.0	2C31	3.05	.26	1.58	2.01	23.90			3	24	28	.09		.06			
469.0	474.0	72249	5.0	.0	2C31	3.20	.14	1.23	3.53	14.90			3	18	21	.15		.03			
474.0	479.0	72250	5.0	.0	2D01	3.26	.10	1.46	3.39	14.40			3	18	21	.16		.03			
479.0	484.0	72251	5.0	.0	2C3	3.40	.07	.60	1.55	9.80			3	18	21	.12		.03			
484.0	489.0	72252	5.0	.0	2D01	3.05	.08	1.10	3.52	9.00			3	18	21	.13		.03			
489.0	494.0	72253	5.0	.0	2C0	3.50	.09	.09	1.27	3.60			2	21	23	.09		.01			
494.0	499.0	72254	5.0	.0	2A31	3.37	.07	.20	1.22	6.20			2	21	23	.10		.01			
499.0	504.0	72255	5.0	.0	2A43	3.19	.08	1.56	4.31	14.10			2	21	23	.14		.01			
504.0	509.0	72256	5.0	.0	2A43	3.43	.09	1.39	2.97	13.60			2	21	23	.10		.01			
509.0	514.0	72257	5.0	.0	2C31	3.45	.21	.12	1.24	6.80			2	24	26	.09		.02			
514.0	519.0	72258	5.0	.0	2A3	3.45	.09	.78	1.77	9.40			2	24	26	.11		.02			
519.0	524.0	72259	5.0	.0	2A31	3.73	.09	.26	1.24	8.50			2	24	26	.07		.02			
524.0	529.0	72260	5.0	.0	2C31	3.58	.08	2.14	3.63	12.60			2	24	26	.07		.02			
529.0	534.0	72261	5.0	.0	2C31	3.97	.14	1.11	2.32	8.10			2	27	29	.03		.02			
534.0	539.0	72262	5.0	.0	2C39	3.76	.31	.63	2.35	7.90			2	27	29	.04		.02			
539.0	544.0	72263	5.0	.0	2C39	3.65	.21	.16	.75	5.10			2	27	29	.06		.02			
544.0	549.0	72264	5.0	.0	2C3	3.45	.12	.10	.95	6.10			2	27	29	.05		.02			
549.0	554.0	72265	5.0	.0	2C31	3.91	.14	.19	2.34	4.90			1	31	33	.03		.01			
554.0	559.0	72266	5.0	.0	2C3	4.00	.17	.07	1.85	4.40			1	31	33	.03		.01			
559.0	564.0	72267	5.0	.0	2C3	3.90	.07	.10	1.20	4.30			1	31	33	.06		.01			
564.0	569.0	72268	5.0	.0	2C3	4.02	.05	.37	2.17	7.00			1	31	33	.03		.01			
569.0	574.0	72269	5.0	.0	2A13	3.33	.10	1.34	2.18	18.60			2	19	22	.12		.02			
574.0	579.0	72270	5.0	.0	2D01	3.61	.10	3.23	3.20	22.20			2	19	22	.10		.02			
579.0	584.0	72271	5.0	.0	2C0	3.38	.07	.82	2.52	8.50			2	19	22	.17		.02			
584.0	589.0	72272	5.0	.0	2C0	3.21	.08	.44	1.69	9.90			2	19	22	.17		.02			
589.0	594.0	72273	5.0	.0	2C0	3.50	.08	.37	1.95	8.10			3	19	22	.15		.02			
594.0	599.0	72274	5.0	.0	2D43	3.45	.03	3.46	7.43	17.20			3	19	22	.10		.02			
599.0	604.0	72275	5.0	.0	2D43	3.56	.07	2.40	6.57	18.60			3	19	22	.13		.02			
604.0	609.0	72276	5.0	.0	2F41	3.84	.05	3.78	9.47	28.70			3	19	22	.08		.02			
609.0	614.0	72277	5.0	.0	2D41	3.86	.05	4.09	9.94	31.60			2	16	18	.10		.03			
614.0	619.0	72278	5.0	.0	2D41	4.09	.03	6.21	14.70	43.70			2	16	18	.08		.03			
619.0	624.0	72279	5.0	.0	2F41	3.86	.04	4.41	8.85	32.70			2	16	18	.13		.03			
624.0	629.0	72280	5.0	.0	2C01	2.78	.03	.55	.12	22.10			2	16	18	.15		.03			
629.0	634.0	72281	5.0	.0	1D4	2.73	.09	.38	1.24	7.60			4	5	10	.17		.04			
634.0	639.0	72282	5.0	.0	1D4	2.66	.14	1.75	.08	61.30			4	5	10	.11		.04			
639.0	644.0	72283	5.0	.0	1D41	2.76	.21	.67	3.50	15.90			4	5	10	.21		.04			
644.0	649.0	72284	5.0	.0	2C01	2.84	.13	.51	2.11	7.60			4	5	10	.15		.04			
649.0	654.0	72285	5.0	.0	2D01	2.79	.08	2.23	2.91	43.40			3	3	6	.26		.02			
654.0	659.0	72286	5.0	.0	2C01	2.72	.09	.95	3.10	28.30			3	3	6	.34		.02			

DDH: 74-07 UTM-N: 9398.7 UTM-E: 15001.9 UTM-ELEV: 4138.5 TOTAL DEPTH: 777.0 SECTION: 120+000
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

-----DEPTHS-----							-----ASSAYS-----													
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
659.0	664.0	72287	5.0	.0	2C0(	2.75	.13	.65	2.24	13.50		3	3	6	.30		.02			
664.0	669.0	72288	5.0	.0	2D0(	2.85	.05	2.80	6.42	33.50		3	3	6	.26		.02			
669.0	674.0	72289	5.0	.0	2D4	2.87	.08	3.74	7.31	38.30		3	3	7	.17		.04			
674.0	679.0	72290	5.0	.0	2D0	2.77	.12	1.61	2.78	23.10		3	3	7	.18		.04			
679.0	684.0	72291	5.0	.0	1D4(	2.83	.10	.50	2.32	14.20		3	3	7	.19		.04			
684.0	689.0	72292	5.0	.0	2D4	2.61	.13	4.03	7.23	51.60		3	3	7	.12		.04			
689.0	694.0	72293	5.0	.0	2D4(	2.97	.08	4.59	9.52	71.00		5	5	10	.15		.07			
694.0	699.0	72294	5.0	.0	1D4(	2.85	.09	1.13	2.35	21.20		5	5	10	.39		.07			
699.0	704.0	72295	5.0	.0	2D4(	3.33	.06	2.02	7.33	56.10		5	5	10	.08		.07			
704.0	709.0	72296	5.0	.0	2D4(	3.18	.17	3.82	10.05	60.90		5	5	10	.14		.07			
709.0	714.0	72297	5.0	.0	2D0&	2.79	.07	1.59	5.33	25.10		3	3	7	.19		.05			
714.0	719.0	72298	5.0	.0	2D4&	2.81	.07	3.36	7.58	54.20		3	3	7	.14		.05			
719.0	724.0	72299	5.0	.0	2D4&	3.00	.08	3.40	7.60	41.60		3	3	7	.12		.05			
724.0	729.0	72300	5.0	.0	1D4(	2.82	.02	.29	.10	7.10		3	3	7	.27		.05			
729.0	734.0	72301	5.0	.0	1D4(	2.96	.07	1.61	2.45	29.50		3	3	7	.22		.05			

DDH: 74-08 UTM-N: 8002.8 UTM-E: 14796.3 UTM-ELEV: 4017.8 TOTAL DEPTH: 576.0 SECTION: 126
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----						-----ASSAYS-----																	
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.		
395.0	400.0	72307	5.0	.0	2ED	3.59	.17	1.12	4.60	19.30		.07	5	20	26	.14		.07					
400.0	405.0	72308	5.0	.0	2DE4	4.12	.14	5.69	12.94	68.30		.14	5	20	26	.08		.07					
405.0	410.0	72309	5.0	.0	2E14	4.20	.33	5.23	8.03	75.10		.14	5	20	26	.30		.07					
410.0	415.0	72310	5.0	.0	2D0	3.77	.14	1.28	3.13	27.60		.21	2	22	24	.08		.02					
415.0	420.0	72311	5.0	.0	2EC	3.81	.22	.15	.14	10.90		.14	2	22	24	.07		.02					
420.0	425.0	72312	5.0	.0	2C0	3.45	.29	1.01	.14	30.20		.48	2	22	24	.13		.02					
425.0	430.0	72313	5.0	.0	2C0	3.01	.39	.51	.18	20.80			2	21	23	.10		.02					
430.0	435.0	72314	5.0	.0	2CF	3.84	.20	3.31	3.36	42.30		.27	4	22	26	.14		.28					
435.0	440.0	72315	5.0	.0	1D/2E	3.86	.17	5.44	4.39	63.60		.41	4	22	26	.42		.28					
440.0	445.0	72316	5.0	.0	2ED4	3.68	.20	5.93	4.29	65.70		.41	4	22	26	.71		.28					
445.0	450.0	72317	5.0	.0	2GD4	4.31	.13	6.05	5.76	82.00			4	22	26	12.11		.28					
450.0	455.0	72318	5.0	.0	2B0	2.81	.04	.99	1.04	13.90			4	10	14	4.41		.17					
455.0	460.0	72319	5.0	.0	2B0	2.69	.04	.59	.72	10.10			4	10	14	3.97		.17					
460.0	465.0	72320	5.0	.0	2B0	2.77	.04	.40	.48	7.00			4	10	14	2.18		.17					
465.0	470.0	72321	5.0	.0	2B4	4.67	.31	5.26	4.97	76.50			4	10	14	.09		.17					
470.0	475.0	72322	5.0	.0	2B0	2.69	.03	.28	.39	5.50		.07	4	4	9	2.26		.22					
482.0	487.0	72324	5.0	.0	2DB	3.12	.08	4.64	4.21	70.30		.07	4	4	9	8.21		.22					
487.0	492.0	72325	5.0	.0	2D0	3.01	.12	3.38	3.37	53.40		.07	21	16	37	4.47		.16					
492.0	497.0	72326	5.0	.0	2H4	4.25	.29	4.74	7.81	69.60		.07	21	16	37	1.37		.16					
497.0	502.0	72327	5.0	.0	2H4	4.33	.35	2.99	3.53	40.50		.01	21	16	37	.05		.16					
502.0	507.0	72328	5.0	.0	2EG	4.63	.21	2.40	3.22	34.60		.01	21	16	37	1.27		.16					
507.0	512.0	72329	5.0	.0	2E0	4.80	.10	1.23	.85	16.40		.01	12	30	42	.04		.10					
512.0	517.0	72330	5.0	.0	2E4	4.86	.14	2.25	3.10	24.20		.01	12	30	42	.12		.10					
517.0	522.0	72331	5.0	.0	2E4	4.80	.12	5.19	7.48	47.70		.01	12	30	42	.05		.10					
522.0	527.0	72332	5.0	.0	2E4	4.26	.29	3.08	6.83	30.90		.01	12	30	42	.06		.10					
527.0	532.0	72333	5.0	.0	2E4	4.13	.27	1.57	3.50	20.80		.07	14	22	36	.10		.12					
532.0	537.0	72334	5.0	.0	2F0	4.55	.16	2.05	3.29	20.90		.07	14	22	36	.02		.12					
537.0	542.0	72335	5.0	.0	2HF	4.36	.26	2.49	4.69	20.10		.21	14	22	36	.03		.12					
542.0	547.0	72336	5.0	.0	2D0	3.00	.13	1.18	2.94	18.50		.14	14	22	36	.31		.12					
547.0	552.0	72337	5.0	.0	2A4	2.83	.12	.90	3.26	27.40		.14	5	6	12	.27		.06					
552.0	557.0	72338	5.0	.0	2D0	3.18	.20	1.88	3.35	48.70		.14	5	6	12	.22		.06					
557.0	562.0	72339	5.0	.0	2A4	2.86	.10	1.53	3.74	37.30		.34	5	6	12	.31		.06					
562.0	567.0	72340	5.0	.0	2B4/0	3.67	.05	29.40	2.12	642.20		.14	5	6	12	.20		.06					
567.0	572.0	72341	5.0	.0	2A4	2.86	.14	2.88	4.74	66.70		.07	5	6	12	.24		.06					

DDH: 74-10 UTM-N: 7890.6 UTM-E: 15456.5 UTM-ELEV: 4017.3 TOTAL DEPTH: 508.0 SECTION: 130
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS----						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
227.7	230.0	72377	2.3	.0	2CF	3.38	.10	2.33	3.78	34.10		.03	3	8	11	.64		.06			
230.0	234.8	72378	4.8	.0	2E0	2.85	.03	.22	.20	2.70		.03	3	8	11	4.80		.06			
276.0	281.0	72380	5.0	.0	2E3	3.99	.39	.66	.48	19.50			6	18	25	.37		.18			
281.0	286.0	72381	5.0	.0	2GE	4.78	.06	5.43	9.33	62.70		.07	6	18	25	33.59		.18			
286.0	296.0	72382	10.0	.0	2GE	4.52	.26	3.20	6.23	44.80		.14	12	19	32	18.38		.10			
296.0	301.0	72383	5.0	.0	2E4	4.41	.48	4.89	5.51	84.70		.07	12	19	32	.26		.10			
301.0	306.0	72384	5.0	.0	2H4	4.16	.51	4.20	3.73	56.90		.07	12	19	32	1.05		.10			
306.0	311.0	72385	5.0	.0	2E3	3.90	.47	2.20	1.71	40.10		.14	8	29	37	.18		.20			
311.0	316.0	72386	5.0	.0	2E8	4.72	.14	1.14	2.29	19.90		.48	8	29	37	.10		.20			
316.0	321.0	72387	5.0	.0	2E8	3.87	.27	.47	.83	6.50			8	29	37	.11		.20			
321.0	326.0	72388	5.0	.0	2E1	4.52	.34	1.02	.62	20.50			8	29	37	.02		.20			
326.0	331.0	72389	5.0	.0	2E1	4.27	.30	1.53	.48	19.80			7	27	35	.08		.14			
331.0	336.0	72390	5.0	.0	2E4	3.91	.26	1.93	2.70	25.60			7	27	35	.04		.14			
336.0	341.0	72391	5.0	.0	2F0	4.12	.21	3.28	4.98	45.90		.34	7	27	35	.02		.14			
341.0	346.0	72392	5.0	.0	2E4	4.18	.24	1.31	4.76	16.50		.27	7	27	35	.04		.14			
346.0	351.0	72393	5.0	.0	2E4	4.11	.19	3.83	6.20	31.70		.27	5	30	35	.02		.21			
351.0	356.0	72394	5.0	.0	2F1	4.57	.37	1.83	1.19	24.40		.07	5	30	35	.03		.21			
356.0	361.0	72395	5.0	.0	2E4	3.99	.25	1.83	3.19	18.00		.55	5	30	35	.03		.21			
361.0	366.0	72396	5.0	.0	2E8	4.16	.32	3.18	5.54	21.40		.07	5	30	35	.02		.21			
366.0	371.0	72397	5.0	.0	2F0	4.39	.27	3.04	2.75	16.10		.01	4	30	34	.03		.16			
371.0	376.0	72398	5.0	.0	2E4	4.62	.15	4.34	4.55	30.40		.01	4	30	34	.02		.16			
376.0	381.0	72399	5.0	.0	2CE	3.78	.31	1.10	1.50	11.50		.96	4	30	34	.02		.16			
381.0	386.0	72400	5.0	.0	2CE	3.86	.23	1.10	2.17	12.40		.41	4	30	34	.02		.16			
386.0	391.0	72401	5.0	.0	2CE	4.06	.06	3.87	12.75	14.20		.01	3	22	25	.04		.04			
391.0	396.0	72402	5.0	.0	2F4	3.81	.06	4.09	10.43	14.60		.07	3	22	25	.11		.04			
396.0	401.0	72403	5.0	.0	2E4	3.47	.04	2.61	7.54	16.60		.07	3	22	25	.13		.04			
401.0	406.0	72404	5.0	.0	2F0	4.34	.11	3.06	6.24	19.80		.21	3	22	25	.05		.04			
406.0	411.0	72405	5.0	.0	2E4	3.87	.02	2.68	8.45	16.30		.07	3	22	25	.08		.06			
411.0	416.0	72406	5.0	.0	2FE4	4.53	.03	5.25	9.75	28.00		.41	3	22	25	.04		.06			
416.0	421.0	72407	5.0	.0	2E4	4.05	.04	3.42	6.74	19.30		.14	3	22	25	.08		.06			
421.0	426.0	72408	5.0	.0	2C0	2.75	.04	.20	.48	4.90		.07	3	22	25	.35		.06			
426.0	431.0	72409	5.0	.0	2C0	3.04	.05	.23	.43	8.90		.14	5	15	20	.17		.04			
431.0	436.0	72410	5.0	.0	2C0	3.32	.14	1.83	.81	20.90		.07	5	15	20	.12		.04			
436.0	441.0	72411	5.0	.0	2CD	3.51	.06	1.97	5.14	14.30		.14	5	15	20	.12		.04			
441.0	446.0	72412	5.0	.0	2D4	3.18	.25	3.59	10.27	21.10		.14	5	15	20	.10		.04			
446.0	451.0	72413	5.0	.0	2A0	2.75	.15	.50	1.56	9.20			5	6	12	.24		.05			
451.0	456.0	72414	5.0	.0	2A0	3.13	.19	.28	1.88	12.80			5	6	12	.18		.05			

DDH: 74-11 UTM-N: 7682.8 UTM-E: 15538.8 UTM-ELEV: 4017.9 TOTAL DEPTH: 300.0 SECTION: 131
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														S.G. W.R.
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	
159.5	164.7	72419	5.2	.0	****	3.28	.27	.14	.15	6.70		.03	10	11	21	.32		.12			
164.7	167.1	72420	2.4	.0	1D49	2.96	.09	2.33	1.44	56.80		.03	10	11	21	1.30		.12			
167.1	170.5	72421	3.4	.0	2D0	3.45	.06	2.52	4.50	49.20		.03	6	6	13	1.05		.12			
170.5	175.5	72422	5.0	.0	2L0	2.81	.02	.06	.08	1.00		.03	6	6	13	2.47		.12			
175.5	177.6	72423	2.1	.0	2D6	3.62	.07	2.97	1.59	50.00		.03	6	6	13	14.02		.12			
177.6	182.8	72424	5.2	.0	2L0	2.81	.03	.29	.18	4.20		.03	6	6	13	1.82		.12			
182.8	185.0	72425	2.2	.0	2B4	3.52	.05	4.40	4.70	70.80			6	6	13	11.75		.12			
185.0	188.1	72426	3.1	.0	2L0	2.99	.04	.62	.55	10.70			6	6	13	6.12		.12			
188.1	193.0	72427	4.9	.0	2L0	2.97	.03	.33	.10	1.80			5	4	9	3.90		.07			
193.0	196.2	72428	3.2	.0	0Q0	2.88	.01	.18	.08	.10			5	4	9	7.44		.07			
196.2	201.0	72429	4.8	.0	1D0	2.73	.01	.10	.13	.10			5	4	9	4.03		.07			
201.0	206.0	72430	5.0	.0	2DH4	3.32	.12	3.78	7.73	53.30			5	4	9	1.69		.07			
206.0	211.0	72431	5.0	.0	2F4	4.67	.11	7.14	11.90	50.10			3	30	33	.18		.05			
211.0	216.0	72432	5.0	.0	2F4	4.73	.02	3.28	8.71	21.80			3	30	33	.02		.05			
216.0	221.0	72433	5.0	.0	2F4	4.80	.08	3.45	9.17	25.00			3	30	33	.02		.05			
221.0	226.0	72434	5.0	.0	2F4	4.75	.09	6.47	10.90	48.10			3	30	33	.05		.05			
226.0	231.0	72435	5.0	.0	2F4	4.86	.05	5.10	12.06	36.70			3	30	33	.02		.05			
231.0	236.0	72436	5.0	.0	2F4	4.81	.07	3.44	6.68	24.50			2	30	33	.02		.05			
236.0	241.0	72437	5.0	.0	2F4	4.84	.06	3.56	6.65	31.90			2	30	33	.03		.05			
241.0	246.0	72438	5.0	.0	2HF4	4.20	.40	1.90	6.50	36.20			2	30	33	.29		.05			
246.0	251.0	72439	5.0	.0	2HF4	4.37	.29	4.49	8.61	41.60			2	30	33	2.00		.05			
251.0	256.0	72440	5.0	.0	2F0	4.00	.20	2.34	5.31	17.40			16	10	26	.18		.08			
256.0	261.0	72441	5.0	.0	2D0	3.09	.13	1.81	6.43	17.10			16	10	26	.37		.08			
261.0	266.0	72442	5.0	.0	2D0	3.16	.10	4.08	3.76	56.60			16	10	26	.46		.08			
266.0	271.0	72443	5.0	.0	2D0	3.05	.11	1.81	2.64	29.00			16	10	26	.38		.08			
271.0	276.0	72444	5.0	.0	2D0	2.95	.07	2.37	3.09	39.40			4	5	10	.23		.04			
276.0	281.0	72445	5.0	.0	2D0	2.98	.07	4.00	4.45	72.20			4	5	10	.23		.04			
281.0	286.0	72446	5.0	.0	2DA	2.78	.06	1.46	4.18	29.70			4	5	10	.29		.04			
286.0	291.0	72447	5.0	.0	2A0	2.87	.21	.98	.84	52.30			4	5	10	7.19		.04			
291.0	296.0	72448	5.0	.0	2A0	2.64	.05	.76	1.14	9.70			2	2	4	.47		.03			
296.0	300.0	72449	4.0	.0	2B4	2.77	.04	1.16	4.06	15.80			2	2	4	.23		.03			

DDH: 74-15 UTM-N: 9004.0 UTM-E: 14601.9 UTM-ELEV: 4056.9 TOTAL DEPTH: 754.0 SECTION: 120+000
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %
501.0	506.0	72484	5.0	.0	2C09	3.08	.54	.12	.18	10.00			8	20	28	.11		.23		
506.0	511.0	72485	5.0	.0	2C09	3.42	.21	.14	.22	6.60			8	20	28	.07		.23		
511.0	516.0	72486	5.0	.0	2C09	3.60	.13	3.20	4.43	40.70			8	20	28	.15		.23		
516.0	521.0	72487	5.0	.0	2F4	4.34	.19	7.00	8.46	95.90			8	20	28	.92		.23		
521.0	526.0	72488	5.0	.0	2H46	3.98	.24	6.81	10.81	102.40			8	20	28	3.18		.23		
526.0	531.0	72489	5.0	.0	2D60	3.27	.19	2.51	1.60	39.90			13	14	28	3.28		.31		
531.0	536.0	72490	5.0	.0	2D46	3.97	.22	5.46	7.61	86.70			13	14	28	1.93		.31		
536.0	541.0	72491	5.0	.0	2E43	3.91	.21	5.38	6.50	82.40			13	14	28	3.02		.31		
541.0	546.0	72492	5.0	.0	2E43	3.90	.16	7.56	4.30	134.70			13	14	28	4.46		.31		
546.0	551.0	72493	5.0	.0	2E46	3.99	.17	5.28	5.94	91.60			11	19	30	1.39		.36		
551.0	556.0	72494	5.0	.0	2E402	3.36	.26	3.36	2.67	77.20			11	19	30	1.39		.36		
556.0	561.0	72495	5.0	.0	2E49	3.80	.27	3.45	1.70	77.30			11	19	30	.54		.36		
561.0	566.0	72496	5.0	.0	2E80	3.81	.17	2.00	1.10	70.60			11	19	30	.63		.36		
566.0	571.0	72497	5.0	.0	2E08	4.46	.20	2.16	1.60	47.70			4	14	19	.31		.18		
571.0	576.0	72498	5.0	.0	2G00	3.95	.22	3.59	2.80	68.30			4	14	19	3.55		.18		
576.0	581.0	72499	5.0	.0	2B46	3.07	.22	1.29	1.07	43.30			4	14	19	7.48		.18		
581.0	586.0	72500	5.0	.0	2B40	2.89	.09	2.52	1.24	59.60			4	14	19	6.91		.18		
586.0	591.0	72501	5.0	.0	2E49	4.27	.20	4.53	3.75	64.00			5	31	37	1.27		.20		
591.0	596.0	72502	5.0	.0	2E49	4.34	.32	3.00	4.70	49.60			5	31	37	7.37		.20		
596.0	601.0	72503	5.0	.0	2E98	4.67	.55	1.02	2.48	12.60			5	31	37	.05		.20		
601.0	606.0	72504	5.0	.0	2F00	4.70	.25	1.78	4.17	12.00			5	31	37	.02		.20		
606.0	611.0	72505	5.0	.0	2F40	4.81	.10	3.11	6.26	21.10			3	35	39	.04		.15		
611.0	616.0	72506	5.0	.0	2F40	4.74	.19	4.95	8.33	32.90			3	35	39	.03		.15		
616.0	621.0	72507	5.0	.0	2E48	4.86	.36	2.73	3.95	20.90			3	35	39	.02		.15		
621.0	626.0	72508	5.0	.0	2F4	4.86	.07	5.35	7.21	32.30			3	35	39	.02		.15		
626.0	631.0	72509	5.0	.0	2E19	4.78	.23	2.45	3.82	23.80			6	34	40	.03		.34		
631.0	636.0	72510	5.0	.0	2E89	4.71	.34	1.18	2.74	18.80			6	34	40	.03		.34		
636.0	641.0	72511	5.0	.0	2E89	4.73	.32	1.92	4.29	19.10			6	34	40	.07		.34		
641.0	646.0	72512	5.0	.0	2E19	4.51	.22	1.72	1.66	18.30			6	34	40	.08		.34		
646.0	651.0	72513	5.0	.0	2E19	4.59	.37	1.64	2.46	16.00			3	35	39	.03		.16		
651.0	656.0	72514	5.0	.0	2F4	4.78	.18	4.63	6.36	28.00			3	35	39	.03		.16		
656.0	661.0	72515	5.0	.0	2F40	4.69	.19	5.43	5.13	38.80			3	35	39	.03		.16		
661.0	666.0	72516	5.0	.0	2E40	4.57	.15	2.89	3.91	29.10			3	35	39	.04		.16		
666.0	671.0	72517	5.0	.0	2F0	4.43	.12	2.16	5.30	16.00			6	32	38	.05		.19		
671.0	676.0	72518	5.0	.0	2E43	4.25	.39	2.66	3.93	24.60			6	32	38	.09		.19		
676.0	681.0	72519	5.0	.0	2E18	4.44	.46	.72	2.46	19.20			6	32	38	.03		.19		
681.0	686.0	72520	5.0	.0	2E89	4.31	.39	1.20	2.23	6.80			6	32	38	.11		.19		
686.0	691.0	72521	5.0	.0	2E43	4.28	.31	1.74	2.60	7.80			3	34	37	.20		.08		
691.0	696.0	72522	5.0	.0	2F40	4.94	.04	3.02	5.25	14.80			3	34	37	.04		.08		
696.0	701.0	72523	5.0	.0	2F40	4.78	.04	3.14	5.83	16.30			3	34	37	.04		.08		
701.0	706.0	72524	5.0	.0	2F40	4.90	.09	3.93	7.64	17.00			3	34	37	.02		.08		
706.0	711.0	72525	5.0	.0	2F40	5.03	.09	3.52	7.77	16.80			6	25	32	.01		.03		
711.0	716.0	72526	5.0	.0	2E43	4.81	.07	3.09	5.22	17.10			6	25	32	.02		.03		
716.0	721.0	72527	5.0	.0	2H90	4.25	.32	1.74	3.33	14.60			6	25	32	.06		.03		
721.0	726.0	72528	5.0	.0	2A00	3.04	.13	1.40	2.76	24.10			6	25	32	.29		.03		
726.0	731.0	72529	5.0	.0	2A0	3.03	.21	.08	.22	5.00			7	8	16	.21		.03		
731.0	736.0	72530	5.0	.0	2A0	3.07	.19	.38	.58	7.30			7	8	16	.14		.03		
736.0	741.0	72531	5.0	.0	2D47	3.15	.10	3.44	7.15	33.70			7	8	16	.08		.03		
741.0	743.0	72532	2.0	.0	2C0	3.33	.10	.65	1.06	8.20			7	8	16	.13		.03		

DDH: 74-17 UTM-N: 8431.2 UTM-E: 14404.4 UTM-ELEV: 4031.0 TOTAL DEPTH: 585.0 SECTION: 122+020
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

-----DEPTHS----						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
484.0	489.0	72541	5.0	.0	2D4	3.43	.08	5.49	15.00	32.90			6	12	19	.81		.20			
489.0	494.0	72542	5.0	.0	2E49	4.55	.20	6.48	7.90	72.50			6	12	19	5.00		.20			
494.0	499.0	72543	5.0	.0	2Q96	3.54	.17	3.63	4.52	51.40			6	12	19	11.75		.20			
499.0	504.0	72544	5.0	.0	2Q96	2.98	.04	.68	.94	10.00			6	12	19	10.06		.20			
504.0	509.0	72545	5.0	.0	2Q89	3.51	.27	3.91	6.13	55.50			8	20	28	6.12		.32			
509.0	514.0	72546	5.0	.0	2G40	4.56	.16	5.15	6.52	78.80			8	20	28	17.34		.32			
514.0	519.0	72547	5.0	.0	2G49	4.58	.33	5.76	6.43	89.00			8	20	28	9.84		.32			
519.0	524.0	72548	5.0	.0	2E40	4.71	.17	6.17	7.05	105.80			8	20	28	1.47		.32			
524.0	529.0	72549	5.0	.0	2E40	4.30	.08	5.02	6.26	80.30			5	13	18	.13		.18			
529.0	534.0	72550	5.0	.0	2B40	2.89	.10	2.54	4.87	35.10			5	13	18	.19		.18			
534.0	539.0	72551	5.0	.0	2E41	3.47	.18	3.33	4.70	57.60			5	13	18	.28		.18			
539.0	544.0	72552	5.0	.0	2D08	2.96	.06	2.85	4.26	79.70			5	13	18	.31		.18			
544.0	549.0	72553	5.0	.0	2D08	3.00	.15	3.26	3.70	66.80			5	5	10	.54		.12			
549.0	554.0	72554	5.0	.0	2D08	3.12	.09	4.27	3.77	106.00			5	5	10	.34		.12			
554.0	559.0	72555	5.0	.0	2D08	3.06	.06	2.00	4.75	53.60			5	5	10	.26		.12			
559.0	564.0	72556	5.0	.0	2D08	3.10	.06	7.01	4.32	555.00			5	5	10	.33		.12			
564.0	569.0	72557	5.0	.0	0Q90	2.91	.04	2.91	2.16	62.50			4	5	9	.37		.05			
569.0	574.0	72558	5.0	.0	2D50	3.00	.15	2.33	3.31	53.40			4	5	9	.36		.05			
574.0	579.0	72559	5.0	.0	2E00	2.84	.11	1.14	2.10	45.90			4	5	9	.33		.05			
579.0	585.0	72560	6.0	.0	0Q90	2.84	.04	1.89	.28	27.40			3	2	5	.29		.03			

DDH: 74-18 UTM-N: 7445.1 UTM-E: 15512.9 UTM-ELEV: 4015.5 TOTAL DEPTH: 250.0 SECTION: 132
RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----								-----ASSAYS-----													
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
124.0	129.0	72563	5.0	.0	2D0	3.65	.11	2.33	5.85	30.60		.14	11	13	25	.15		.09			
129.0	134.0	72564	5.0	.0	2E4	4.64	.16	3.57	6.39	40.40		.07	11	13	25	.05		.09			
134.0	139.0	72565	5.0	.0	2H4	4.22	.40	3.19	4.65	45.80		.07	11	13	25	.03		.09			
139.0	144.0	72566	5.0	.0	2H4	4.58	.37	5.05	6.82	67.20		.14	11	13	25	.05		.09			
144.0	149.0	72567	5.0	.0	2B0	4.76	.32	1.80	2.98	21.90		.01	10	7	17	.07		.04			
149.0	154.0	72568	5.0	.0	2B4	3.22	.20	.90	4.11	14.40		.07	10	7	17	.57		.04			
154.0	159.0	72569	5.0	.0	2B4	3.03	.11	1.29	2.78	21.60		.01	10	7	17	.45		.04			
159.0	164.0	72570	5.0	.0	2A0	3.06	.14	1.20	2.73	19.40		.21	10	7	17	.78		.04			
164.0	168.0	72571	4.0	.0	2A4	3.11	.03	1.37	6.07	23.30		.27	3	7	11	.48		.03			
168.0	173.0	72572	5.0	.0	2A4	3.05	.02	2.13	1.99	45.60		.62	3	7	11	.45		.03			
173.0	178.0	72573	5.0	.0	2A0	2.99	.05	1.40	2.52	28.80		.34	3	7	11	.42		.03			
178.0	183.0	72574	5.0	.0	2A0	2.68	.02	.66	1.57	12.30			3	7	11	.60		.03			
183.0	188.0	72575	5.0	.0	2A0	2.75	.06	.75	1.49	19.40			3	4	7	.37		.02			
188.0	191.5	72576	3.5	.0	2A0	2.88	.07	.37	.22	11.70			3	4	7	.24		.02			

DDH: 74-19 UTM-N: 7431.3 UTM-E: 15336.4 UTM-ELEV: 4016.4 TOTAL DEPTH: 373.0 SECTION: 131
RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
231.0	236.0	72582	5.0	.0	2C0	3.34	.40	.80	.11	15.60			8	8	17	.02		.05			
236.0	241.0	72583	5.0	.0	2D0	2.78	.09	1.20	5.32	49.40		.27	8	8	17	.05		.05			
241.0	246.0	72584	5.0	.0	2D0	3.39	.14	2.33	3.07	48.00		.07	8	8	17	.33		.05			
246.0	251.0	72585	5.0	.0	2D0	3.79	.09	2.83	3.73	37.50		.14	5	10	16	.24		.06			
251.0	256.0	72586	5.0	.0	2C0	3.37	.16	1.48	1.92	36.00		.07	5	10	16	.81		.06			
256.0	261.0	72587	5.0	.0	2C2	2.98	.08	.80	2.02	21.70		.62	5	10	16	1.03		.06			
261.0	266.0	72588	5.0	.0	2D0	2.99	.10	1.58	2.68	38.90		.07	5	10	16	.63		.06			
266.0	271.0	72589	5.0	.0	2D0	3.06	.11	2.63	4.93	68.40		.07	4	4	9	.62		.04			
271.0	276.0	72590	5.0	.0	2A0	2.96	.10	1.04	2.80	36.80		.34	4	4	9	.47		.04			
276.0	281.0	72591	5.0	.0	2A0	2.77	.04	.66	1.22	13.90			4	4	9	.50		.04			
281.0	286.0	72592	5.0	.0	2A0	2.98	.11	.60	1.14	19.80			4	4	9	.23		.04			
286.0	288.0	72593	2.0	.0	2A0	2.84	.07	.42	.66	13.80			4	4	9	.30		.04			

DDH: 74-20 UTM-N: 7690.8 UTM-E: 15281.2 UTM-ELEV: 4004.4 TOTAL DEPTH: 427.0 SECTION: 130
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

---DEPTHS---						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
219.0	224.0	72599	5.0	.0	2C0	3.45	.42	.50	.44	10.20			2	24	26	.11		.04			
224.0	229.0	72600	5.0	.0	2C0	3.49	.10	.46	2.95	7.90		.14	2	24	26	.12		.04			
229.0	234.0	72601	5.0	.0	2C0	4.29	.33	.66	2.24	13.30		.01	2	24	26	.12		.04			
234.0	239.0	72602	5.0	.0	2E3	4.94	.02	.28	.74	6.50		.48	3	22	25	.03		.16			
239.0	244.0	72603	5.0	.0	2E4	4.37	.17	5.70	6.79	81.00		.34	3	22	25	.36		.16			
244.0	249.0	72604	5.0	.0	2D6	3.19	.10	2.30	2.56	37.90		.48	3	22	25	2.25		.16			
249.0	254.0	72605	5.0	.0	2D6	3.17	.04	3.39	3.39	67.60		.14	3	22	25	6.07		.16			
254.0	259.0	72606	5.0	.0	2E4	4.17	.23	3.43	4.76	52.30		.21	21	21	43	.31		.14			
259.0	264.0	72607	5.0	.0	2H4	4.50	.40	2.20	3.51	29.60		1.78	21	21	43	.03		.14			
264.0	269.0	72608	5.0	.0	2H4	4.54	.33	3.43	5.24	41.00		.14	21	21	43	.02		.14			
269.0	274.0	72609	5.0	.0	2H4	4.74	.20	2.35	4.14	27.00		.07	21	21	43	.10		.14			
274.0	279.0	72610	5.0	.0	2E4	4.64	.45	3.14	4.90	19.90		.07	6	34	40	.12		.05			
279.0	284.0	72611	5.0	.0	2H4	4.98	.07	3.02	5.44	16.50		.01	6	34	40	.04		.05			
284.0	289.0	72612	5.0	.0	2EF	4.88	.03	3.80	5.24	20.20		.21	6	34	40	.03		.05			
289.0	294.0	72613	5.0	.0	2EF	4.78	.04	2.30	4.00	15.60		.34	6	34	40	.08		.05			
294.0	299.0	72614	5.0	.0	2BC	3.18	.14	1.80	3.49	33.90		.34	6	34	40	.42		.05			

DDH: 74-21 UTM-N: 7191.9 UTM-E: 15402.4 UTM-ELEV: 4014.0 TOTAL DEPTH: 250.0 SECTION: 133
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

						-----ASSAYS-----															
---DEPTHS---		SAMPLE	INT.	REC.	ROCK	S.G.	Cu	Pb	Zn	Ag(AA)	Ag(FA)	Au(FA)	Po	Py	TOT	BaO	Hg	Mn	As	Ba	S.G.
FROM	TO	NO.			UNIT	PULP	%	%	%	g/mT	g/mT	g/mT	%	%	Fe	%	%	%	%	%	W.R.
99.0	104.0	72619	5.0	.0	2F0	4.37	.18	3.70	3.41	40.50		.34				1.52					
104.0	109.0	72620	5.0	.0	2F4	3.10	.22	6.20	6.14	76.50		.14	7	14	21	1.17		.22			
109.0	114.0	72621	5.0	.0	2F0	3.52	.15	4.08	4.87	55.00		.01	7	14	21	.76		.22			
114.0	119.0	72622	5.0	.0	2D34	3.43	.11	4.10	5.92	59.50		.01	7	14	21	.89		.22			
119.0	124.0	72623	5.0	.0	2C0	3.02	.10	.42	1.08	6.80		.01	7	14	21	3.28		.22			
124.0	127.0	72624	3.0	.0	2E47	4.38	.32	1.56	2.63	24.60			17	22	40	.46		.12			
131.5	135.7	72626	4.2	.0	2C3	2.79	.08	1.17	1.16	25.30			5	4	9	4.85		.03			
135.7	136.3	72627	.6	.0	2H4	4.03	.42	5.46	7.25	83.50			17	22	40	.14		.12			
139.0	144.0	72629	5.0	.0	2B4	4.03	.42	5.46	7.25	83.50			17	22	40	.14		.12			
144.0	149.0	72630	5.0	.0	2A4	3.23	.25	3.70	5.06	58.40			4	4	8	.33		.06			
149.0	154.0	72631	5.0	.0	2A0	2.71	.09	.51	.89	14.60			4	4	8	.74		.06			
154.0	159.0	72632	5.0	.0	2A0	2.56	.06	.26	.34	10.30			4	4	8	.49		.06			
159.0	164.0	72633	5.0	.0	2A0	2.69	.05	2.96	.97	59.90			4	4	8	1.31		.06			
164.0	169.0	72634	5.0	.0	2A0	2.57	.03	.30	.23	13.90			2	1	4	1.38		.01			
169.0	174.0	72635	5.0	.0	2A0	2.66	.06	.34	.75	10.00			2	1	4	.76		.01			
174.0	179.0	72636	5.0	.0	2A0	2.65	.04	.94	1.21	14.20			2	1	4	.74		.01			
179.0	184.0	72637	5.0	.0	2A0	2.57	.03	1.13	1.51	12.60		.07	2	1	4	.68		.01			
184.0	189.0	72638	5.0	.0	2A0	2.65	.09	1.29	2.55	18.30		.34	3	3	7	.24		.05			
189.0	194.5	72639	5.5	.0	2A0	2.78	.15	.92	1.33	15.80			3	3	7	.22		.05			

DDH: 74005 UTM-N: 9606.3 UTM-E: 14193.3 UTM-ELEV: 3902.6 TOTAL DEPTH: 325.0 SECTION:
 RFE: RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

---DEPTHS---						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
35.0	40.0	72094	5.0	.0	****	3.30	.05	1.86	3.23	41.10			5	7	13	10.22		.08			
40.0	45.0	72095	5.0	.0	****	2.96	.09	.24	.28	10.30			5	7	13	4.17		.08			
45.0	50.0	72096	5.0	.0	****	4.32	.16	3.69	3.53	69.40			10	25	35	1.74		.31			
50.0	55.0	72097	5.0	.0	****	4.67	.13	4.47	4.48	54.30			10	25	35	7.12		.31			
55.0	60.0	72098	5.0	.0	****	4.76	.08	3.60	4.24	37.70			5	33	39	9.55		.25			
60.0	65.0	72099	5.0	.0	****	4.51	.22	4.75	4.06	85.80			5	33	39	2.58		.25			
65.0	70.0	72100	5.0	.0	****	4.42	.19	3.69	4.94	50.50			5	33	39	11.34		.25			
70.0	75.0	72101	5.0	.0	****	4.74	.26	2.79	2.51	35.60			5	33	39	.40		.25			
75.0	80.0	72102	5.0	.0	****	4.41	.24	2.22	2.30	29.30			9	22	31	.28		.27			
80.0	85.0	72103	5.0	.0	****	4.29	.32	7.45	5.88	102.40			9	22	31	12.40		.27			
85.0	90.0	72104	5.0	.0	****	4.44	.23	5.12	5.21	71.60			9	22	31	9.39		.27			
90.0	95.0	72105	5.0	.0	****	4.35	.19	5.38	5.30	76.90			9	22	31	8.10		.27			
95.0	100.0	72106	5.0	.0	****	4.54	.17	3.75	3.53	47.20			5	27	33	.13		.14			
100.0	105.0	72107	5.0	.0	****	3.47	.05	.40	.36	8.00			5	27	33	.04		.14			
105.0	110.0	72108	5.0	.0	****	4.82	.16	6.31	4.15	61.70			5	27	33	.02		.14			
110.0	115.0	72109	5.0	.0	****	4.87	.20	5.92	5.73	59.10			5	27	33	.04		.14			
115.0	120.0	72110	5.0	.0	****	4.71	.19	2.36	1.68	26.70			3	37	41	.02		.08			
120.0	125.0	72111	5.0	.0	****	4.77	.21	1.40	2.67	17.50			3	37	41	.03		.08			
125.0	130.0	72112	5.0	.0	****	4.39	.16	1.18	1.60	10.20			3	37	41	.04		.08			
130.0	135.0	72113	5.0	.0	****	4.10	.54	1.96	1.28	23.00			4	24	28	.12		.14			
135.0	140.0	72114	5.0	.0	****	4.11	.41	.84	.96	13.40			2	36	39	.17		.09			
140.0	145.0	72115	5.0	.0	****	4.58	.06	.50	.46	6.00			2	36	39	.10		.09			
145.0	150.0	72116	5.0	.0	****	4.60	.06	1.14	.16	8.60			2	36	39	.02		.09			
150.0	155.0	72117	5.0	.0	****	5.04	.30	1.44	3.28	10.50			2	36	39	.02		.09			
155.0	160.0	72118	5.0	.0	****	4.61	.34	2.16	3.70	8.10			6	32	39	.03		.20			
160.0	165.0	72119	5.0	.0	****	4.37	.34	1.16	3.49	9.00			6	32	39	.02		.20			
165.0	170.0	72120	5.0	.0	****	4.46	.44	.48	2.53	6.90			6	32	39	.02		.20			
170.0	175.0	72121	5.0	.0	****	4.38	.17	1.46	3.65	7.00			6	32	39	.03		.20			
175.0	180.0	72122	5.0	.0	****	3.79	.23	2.52	4.03	10.30			3	33	36	.17		.05			
180.0	185.0	72123	5.0	.0	****	4.87	.20	3.84	6.14	15.80			3	33	36	.01		.05			
185.0	190.0	72124	5.0	.0	****	4.89	.07	2.52	4.58	9.70			3	33	36	.01		.05			
190.0	195.0	72125	5.0	.0	****	4.88	.05	2.88	8.04	10.30			3	33	36	.01		.05			
195.0	200.0	72126	5.0	.0	****	4.69	.21	2.94	5.64	9.00			5	35	41	.01		.13			
200.0	205.0	72127	5.0	.0	****	4.62	.13	.40	1.86	4.30			5	35	41	.01		.13			
205.0	210.0	72128	5.0	.0	****	4.53	.16	.36	1.18	3.70			5	35	41	.01		.13			
210.0	215.0	72129	5.0	.0	****	4.82	.24	.82	2.03	6.10			5	35	41	.01		.13			
215.0	220.0	72130	5.0	.0	****	4.38	.29	.74	2.07	11.90			7	33	41	.01		.20			
220.0	225.0	72131	5.0	.0	****	4.79	.33	.96	1.60	13.20			7	33	41	.02		.20			
225.0	230.0	72132	5.0	.0	****	4.46	.23	.42	1.34	7.80			7	33	41	.02		.20			
230.0	235.0	72133	5.0	.0	****	4.73	.46	1.64	3.44	13.20			7	33	41	.02		.20			
235.0	240.0	72134	5.0	.0	****	4.47	.38	1.34	3.21	9.60			2	36	39	.01		.05			
240.0	245.0	72135	5.0	.0	****	4.93	.10	3.93	5.27	19.80			2	36	39	.01		.05			
245.0	250.0	72136	5.0	.0	****	4.93	.07	4.00	6.14	15.20			2	36	39	.01		.05			
250.0	255.0	72137	5.0	.0	****	4.86	.18	4.47	7.21	20.40			2	36	39	.02		.05			
255.0	260.0	72138	5.0	.0	****	3.23	.08	3.39	7.41	23.90			3	18	21	.13		.03			
260.0	265.0	72139	5.0	.0	****	3.46	.04	2.79	4.79	22.70			3	18	21	.11		.03			
265.0	270.0	72140	5.0	.0	****	3.58	.08	4.99	10.81	32.90			3	18	21	.07		.03			
270.0	275.0	72141	5.0	.0	****	4.40	.04	3.33	8.09	22.00			3	18	21	.02		.03			
275.0	280.0	72142	5.0	.0	****	4.95	.02	3.60	7.07	17.60			3	27	30	.01		.04			
280.0	285.0	72143	5.0	.0	****	5.13	.04	3.48	5.36	16.80			3	27	30	.01		.04			
285.0	290.0	72144	5.0	.0	****	3.73	.06	4.31	11.03	19.70			3	27	30	.06		.04			

DDH: 74005 UTM-N: 9606.3 UTM-E: 14193.3 UTM-ELEV: 3902.6 TOTAL DEPTH: 325.0 SECTION:
RFE: RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS----						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
290.0	295.0	72145	5.0	.0	****	3.45	.06	4.99	9.57	23.00				3	27	30	.09		.04		
295.0	300.0	72146	5.0	.0	****	3.49	.06	4.78	12.90	33.50				3	15	19	.09		.04		
300.0	305.0	72147	5.0	.0	****	3.24	.05	2.43	7.24	25.00				3	15	19	.09		.04		
305.0	310.0	72148	5.0	.0	****	3.25	.06	1.36	.88	18.80				3	15	19	.06		.04		
310.0	315.0	72149	5.0	.0	****	3.29	.06	.28	1.24	7.70				3	15	19	.10		.04		
315.0	320.0	72150	5.0	.0	****	3.22	.29	.18	1.52	12.20				6	7	13	.20		.06		
320.0	325.0	72151	5.0	.0	****	2.80	.08	1.58	2.16	29.50				6	7	13	.21		.06		

DDH: 74006 UTM-N: 9815.2 UTM-E: 14343.8 UTM-ELEV: 3979.8 TOTAL DEPTH: 407.0 SECTION:
 RFE: RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														S.G. W.R.
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Pt %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	
27.0	32.0	72154	5.0	.0	****	3.68	.06	3.56	7.09	59.00			5	25	31	.29		.27			
32.0	37.0	72155	5.0	.0	****	4.43	.02	4.14	7.74	52.10			5	25	31	7.68		.27			
37.0	42.0	72156	5.0	.0	****	4.58	.09	6.98	5.73	95.50			5	25	31	26.98		.27			
42.0	47.0	72157	5.0	.0	****	4.48	.13	5.56	4.83	86.80			5	25	31	12.50		.27			
47.0	52.0	72158	5.0	.0	****	4.70	.03	2.55	2.89	46.40			5	25	31	1.36		.27			
52.0	57.0	72159	5.0	.0	****	4.68	.10	5.83	5.60	88.90			4	9	14	19.37		.17			
57.0	62.0	72160	5.0	.0	****	4.64	.08	7.81	7.17	103.30			4	9	14	31.49		.17			
62.0	67.0	72161	5.0	.0	****	3.45	.09	3.20	3.10	54.00			4	9	14	7.37		.17			
67.0	72.0	72162	5.0	.0	****	2.76	.02		.22	3.50			4	9	14	.37		.17			
72.0	77.0	72163	5.0	.0	****	2.72	.03	.01		3.90			3	9	12	.52		.05			
77.0	82.0	72164	5.0	.0	****	2.86	.11	.27	.27	10.40			3	9	12	.59		.05			
82.0	87.0	72165	5.0	.0	****	3.55	.06	2.27	5.33	50.00			3	9	12	.16		.05			
87.0	92.0	72166	5.0	.0	****	3.14	.07	.90	4.59	30.20			3	9	12	.27		.05			
92.0	97.0	72167	5.0	.0	****	2.80	.05	.53	.61	22.20			8	13	22	.74		.05			
97.0	102.0	72168	5.0	.0	****	3.75	.49	1.80	1.26	46.40			8	13	22	.30		.05			
102.0	107.0	72169	5.0	.0	****	4.20	.10	3.37	8.78	35.20			8	13	22	.95		.05			
107.0	112.0	72170	5.0	.0	****	3.32	.07	3.44	4.20	50.20			8	13	22	.23		.05			
112.0	117.0	72171	5.0	.0	****	4.06	.14	2.71	5.79	37.40			2	32	34	.10		.04			
117.0	122.0	72172	5.0	.0	****	4.64	.15	3.04	4.13	31.00			2	32	34	.06		.04			
122.0	127.0	72173	5.0	.0	****	4.66	.36	3.67	4.41	41.80			2	32	34	.05		.04			
127.0	132.0	72174	5.0	.0	****	4.13	.16	2.91	3.71	23.80			2	32	34	.07		.04			
132.0	137.0	72175	5.0	.0	****	4.67	.31	.62	.72	11.90			6	31	38	.04		.20			
137.0	142.0	72176	5.0	.0	****	4.60	.50	1.74	1.79	23.50			6	31	38	.04		.20			
142.0	147.0	72177	5.0	.0	****	4.76	.14	5.31	6.86	26.40			6	31	38	.02		.20			
147.0	152.0	72178	5.0	.0	****	4.36	.14	1.88	3.87	20.80			6	31	38	.03		.20			
152.0	157.0	72179	5.0	.0	****	4.15	.11	1.30	3.03	9.10			5	29	35	.02		.11			
157.0	162.0	72180	5.0	.0	****	3.95	.33		1.47	7.80			5	29	35	.03		.11			
162.0	167.0	72181	5.0	.0	****	4.25	.32		1.22	7.50			5	29	35	.02		.11			
167.0	172.0	72182	5.0	.0	****	4.19	.21		.98	4.70			5	29	35	.02		.11			
172.0	177.0	72183	5.0	.0	****	4.51	.47	.26	1.11	6.40			6	32	38	.04		.12			
177.0	182.0	72184	5.0	.0	****	4.34	.58	.17	.50	12.40			6	32	38	.04		.12			
182.0	187.0	72185	5.0	.0	****	4.60	.16	.22	1.40	2.80			6	32	38	.02		.12			
187.0	192.0	72186	5.0	.0	****	4.27	.07	3.15	6.41	7.80			6	32	38	.02		.12			
192.0	197.0	72187	5.0	.0	****	4.09	.05	5.38	13.38	15.60			3	20	23	.05		.04			
197.0	202.0	72188	5.0	.0	****	4.07	.06	7.53	15.30	23.90			3	20	23	.08		.04			
202.0	207.0	72189	5.0	.0	****	4.02	.04	3.89	9.17	15.00			3	20	23	.04		.04			
207.0	212.0	72190	5.0	.0	****	3.83	.04	3.70	10.71	13.70			3	20	23	.07		.04			
212.0	217.0	72191	5.0	.0	****	4.34	.04	5.76	12.69	21.70			2	26	28	.03		.04			
217.0	222.0	72192	5.0	.0	****	4.47	.03	4.92	9.88	22.90			2	26	28	.03		.04			
222.0	227.0	72193	5.0	.0	****	4.07	.04	2.49	7.07	19.00			2	26	28	.11		.04			
227.0	232.0	72194	5.0	.0	****	4.11	.02	1.66	6.88	12.10			2	26	28	.07		.04			
232.0	237.0	72195	5.0	.0	****	3.71	.04	2.93	7.69	18.30			3	12	16	.12		.04			
237.0	242.0	72196	5.0	.0	****	3.27	.05	1.50	7.66	9.20			3	12	16	.13		.04			
242.0	247.0	72197	5.0	.0	****	3.03	.07	1.37	4.71	14.80			3	12	16	.18		.04			
247.0	252.0	72198	5.0	.0	****	3.19	.05	1.34	3.84	12.60			3	12	16	.12		.04			
252.0	257.0	72199	5.0	.0	****	3.18	.04	.95	5.01	10.30			2	24	27	.18		.04			
257.0	262.0	72200	5.0	.0	****	3.12	.04	.23	1.05	6.60			2	24	27	.24		.04			
262.0	267.0	72201	5.0	.0	****	4.00	.06	.21	4.96	11.20			2	24	27	.04		.04			
267.0	272.0	72202	5.0	.0	****	4.91	.01	1.01	2.99	8.30			2	24	27	.01		.04			
272.0	277.0	72203	5.0	.0	****	4.18	.07	4.40	10.92	26.70			4	19	23	.01		.03			
277.0	282.0	72204	5.0	.0	****	4.18	.04	8.13	18.20	34.50			2	26	28	.02		.02			

DDH: 74006 UTM-N: 9815.2 UTM-E: 14343.8 UTM-ELEV: 3979.8 TOTAL DEPTH: 407.0 SECTION:
RFE: RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														S.G. W.R.
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	
282.0	287.0	72205	5.0	.0	****	4.66	.03	7.73	16.30	33.70			2	26	28	.02		.02			
287.0	292.0	72206	5.0	.0	****	4.83	.02	8.08	12.83	36.10			2	26	28	.02		.02			
292.0	297.0	72207	5.0	.0	****	4.50	.03	8.96	15.00	38.30			2	20	22	.06		.02			
297.0	302.0	72208	5.0	.0	****	3.65	.07	7.47	18.60	35.00			2	20	22	.07		.02			
302.0	307.0	72209	5.0	.0	****	4.42	.05	5.06	8.55	26.40			3	25	28	.02		.02			
307.0	312.0	72210	5.0	.0	****	3.95	.07	7.17	16.90	31.90			4	12	17	.03		.02			
312.0	317.0	72211	5.0	.0	****	4.07	.11	6.33	15.60	28.80			4	16	20	.02		.03			
317.0	322.0	72212	5.0	.0	****	4.88	.03	5.36	7.45	24.30			1	35	37	.01		.01			
322.0	327.0	72213	5.0	.0	****	4.76	.07	3.03	5.66	15.10			1	35	37	.01		.01			
327.0	332.0	72214	5.0	.0	****	4.13	.06	2.52	7.00	17.30			1	35	37	.04		.01			
332.0	337.0	72215	5.0	.0	****	3.21	.06	.82	1.88	9.70			3	26	29	.17		.04			
337.0	342.0	72216	5.0	.0	****	3.54	.06	2.28	4.78	18.10			3	26	29	.04		.04			
342.0	347.0	72217	5.0	.0	****	3.95	.07	.95	2.71	12.80			3	26	29	.03		.04			
347.0	352.0	72218	5.0	.0	****	4.73	.03	2.40	3.95	19.60			3	26	29	.01		.04			
352.0	357.0	72219	5.0	.0	****	4.51	.03	1.78	4.78	16.30			4	30	34	.02		.06			
357.0	362.0	72220	5.0	.0	****	4.34	.08	1.15	3.72	19.20			4	30	34	.06		.06			
362.0	367.0	72221	5.0	.0	****	3.86	.07	.65	3.02	9.40			4	30	34	.05		.06			
367.0	372.0	72222	5.0	.0	****	3.83	.06	2.35	4.38	21.60			4	30	34	.05		.06			
372.0	377.0	72223	5.0	.0	****	3.33	.10	1.73	4.22	16.70			4	18	22	.19		.02			
377.0	382.0	72224	5.0	.0	****	4.03	.05	4.53	11.75	29.00			4	20	24	.08		.02			
382.0	387.0	72225	5.0	.0	****	4.20	.03	3.90	10.00	25.40			4	22	26	.03		.02			
387.0	392.0	72226	5.0	.0	****	3.53	.05	2.31	9.82	19.00			4	18	22	.06		.02			
392.0	397.0	72227	5.0	.0	****	3.09	.05	1.20	3.98	14.00			6	12	18	.13		.07			
397.0	402.0	72228	5.0	.0	****	3.52	.09	3.33	8.79	25.30			6	12	18	.13		.07			
402.0	407.0	72229	5.0	.0	****	3.31	.23	4.82	5.16	56.40			6	12	18	.15		.07			

DDH: 74009 UTM-N: 9404.4 UTM-E: 13993.3 UTM-ELEV: 3923.4 TOTAL DEPTH: 311.0 SECTION:
 RFE: RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	ASSAYS													
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %
171.0	176.0	72345	5.0	.0	****	3.30	.10	1.55	5.01	23.70			7	21	29	.17		.21		
176.0	181.0	72346	5.0	.0	****	3.91	.21	2.06	4.83	29.10			7	21	29	.09		.21		
181.0	186.0	72347	5.0	.0	****	4.40	.22	5.99	8.01	74.60			7	21	29	.11		.21		
186.0	191.0	72348	5.0	.0	****	4.63	.22	6.37	7.04	83.60			7	21	29	.60		.21		
191.0	196.0	72349	5.0	.0	****	4.36	.13	2.98	3.92	43.00			7	21	29	.38		.21		
196.0	201.0	72350	5.0	.0	****	4.25	.26	5.60	6.78	74.50			6	35	42	.22		.26		
201.0	206.0	72351	5.0	.0	****	4.59	.13	4.19	4.99	57.70			6	35	42	.25		.26		
206.0	211.0	72352	5.0	.0	****	4.54	.18	5.98	5.83	82.30			6	35	42	4.51		.26		
211.0	216.0	72353	5.0	.0	****	4.41	.32	4.79	4.59	75.60			6	35	42	.30		.26		
216.0	221.0	72354	5.0	.0	****	4.61	.24	7.75	8.10	93.90			7	23	30	.10		.50		
221.0	226.0	72355	5.0	.0	****	5.02	.18	7.42	7.36	102.50			2	18	21	10.21		.09		
226.0	231.0	72356	5.0	.0	****	4.75	.11	7.64	9.46	89.00			2	18	21	26.78		.09		
231.0	236.0	72357	5.0	.0	****	4.68	.07	6.97	8.46	72.40			2	18	21	29.28		.09		
236.0	241.0	72358	5.0	.0	****	4.65	.13	3.56	4.65	37.90			3	20	23	11.23		.16		
241.0	246.0	72359	5.0	.0	****	4.75	.24	8.43	8.13	100.70			3	20	23	11.30		.16		
246.0	251.0	72360	5.0	.0	****	4.55	.18	10.10	8.67	123.20			3	20	23	14.82		.16		
251.0	256.0	72361	5.0	.0	****	4.76	.11	7.14	8.17	73.50			3	20	23	32.13		.16		
256.0	261.0	72362	5.0	.0	****	4.86	.37	2.20	1.82	26.10			4	34	38	.76		.03		
261.0	266.0	72363	5.0	.0	****	5.35	.19	3.25	4.34	22.20			4	34	38	.05		.03		
266.0	271.0	72364	5.0	.0	****	4.70	.13	5.59	7.59	41.60			4	34	38	.06		.03		
271.0	276.0	72365	5.0	.0	****	4.68	.51	3.42	6.81	40.60			4	34	38	.09		.03		
276.0	281.0	72366	5.0	.0	****	4.45	.68	3.00	5.58	34.80			11	3	15	.07		.04		
281.0	286.0	72367	5.0	.0	****	2.87	.18	2.10	4.39	28.80			11	3	15	.27		.04		
286.0	291.0	72368	5.0	.0	****	2.72	.10	1.18	1.38	9.30			11	3	15	.23		.04		
291.0	296.0	72369	5.0	.0	****	2.69	.05	1.38	2.26	8.60			11	3	15	.24		.04		
296.0	301.0	72370	5.0	.0	****	2.76	.14	1.30	1.88	13.70			4	2	6	.21		.04		
301.0	306.0	72371	5.0	.0	****	2.67	.12	2.10	2.67	21.60			4	2	6	.26		.04		
306.0	311.0	72372	5.0	.0	****	2.78	.13	1.92	2.19	30.60			4	2	6	.29		.04		

PAGE: 88

[illegible]

PAGE: 39

[illegible]

DDH: 75-03 UTM-N: 9214.5 UTM-E: 14972.6 UTM-ELEV: 4139.6 TOTAL DEPTH: 688.0 SECTION: 121+000
 RFE: 92 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

---DEPTHS---						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
529.0	535.0	72715	6.0	.0	2D9&	4.00	.39	3.01	5.26	35.70			3	18	21	.11		.07			
535.0	540.0	72716	5.0	.0	2D4&	3.42	.10	3.30	7.80	3.40			3	18	21	.18		.07			
540.0	545.0	72717	5.0	.0	2E10	3.76	.07	1.91	4.41	18.50			3	18	21	.10		.07			
545.0	550.0	72718	5.0	.0	2C8&	3.48	.17	1.83	3.90	18.50			3	18	21	.10		.07			
550.0	555.0	72719	5.0	.0	2C8&	3.94	.24	.21	.77	10.30			3	24	27	.05		.13			
555.0	560.0	72720	5.0	.0	2C89	3.51	.20	.22	1.08	3.40			3	24	27	.15		.13			
560.0	565.0	72721	5.0	.0	2C39	4.07	.39	.09	1.06	2.70			3	24	27	.06		.13			
565.0	570.0	72722	5.0	.0	2C9&	3.60	.24	.60	2.22	8.20			3	24	27	.09		.13			
570.0	575.0	72723	5.0	.0	2C0&	3.58	.11	.20	.40	10.30			1	21	23	.09		.02			
575.0	580.0	72724	5.0	.0	2C50	3.51	.19	.06	.14	1.40			1	21	23	.10		.02			
580.0	585.0	72725	5.0	.0	2C5	3.58	.18	.29	.90				1	21	23	.11		.02			
585.0	590.0	72726	5.0	.0	2C39	3.91	.21	.48	.70	4.50			1	21	23	.08		.02			
590.0	595.0	72727	5.0	.0	2C39	3.89	.42	.35	.86	3.40			3	16	20	.06		.04			
595.0	600.0	72728	5.0	.0	2D0&	3.64	.06	2.30	6.36	7.50			3	16	20	.09		.04			
600.0	605.0	72729	5.0	.0	2D4&	3.42	.13	3.20	7.58	32.20			3	16	20	.13		.04			
605.0	610.0	72730	5.0	.0	2C0&	2.87	.14	1.40	1.90	17.80			3	16	20	.31		.04			
610.0	615.0	72731	5.0	.0	2L00	2.92	.15	.55	1.31	6.90			3	4	7	.20		.04			
615.0	620.0	72732	5.0	.0	2L0	2.83	.09	.27	.95	8.90			3	4	7	.12		.04			
620.0	625.0	72733	5.0	.0	2L0	2.67	.02	.03	.17	6.20			3	4	7	.15		.04			
625.0	630.0	72734	5.0	.0	2A00	2.82	.04	.86	1.15	15.80			3	4	7	.16		.04			
630.0	635.0	72735	5.0	.0	2A4	2.75	.09	1.65	3.90	32.90			3	4	7	.32		.03			
635.0	640.0	72736	5.0	.0	2A4	2.88	.12	.84	3.60	19.50			3	4	7	.41		.03			
640.0	645.0	72737	5.0	.0	2A4	2.89	.06	1.10	3.60	22.30			3	4	7	.32		.03			
645.0	650.0	72738	5.0	.0	2A0	2.89	.13	1.27	2.20	25.70			3	4	7	.27		.03			
650.0	655.0	72739	5.0	.0	2C00	2.87	.11	.72	1.63	25.00			2	3	6	.24		.02			
655.0	660.0	72740	5.0	.0	2C00	2.86	.09	.70	1.32	20.60			2	3	6	.20		.02			
660.0	665.0	72741	5.0	.0	2A4	2.75	.10	1.60	3.62	34.00			2	1	4	.22		.01			
665.0	670.0	72742	5.0	.0	2A4	2.84	.06	1.06	3.19	16.40			2	1	4	.18		.01			
670.0	675.8	72743	5.8	.0	2A40	2.83	.12	2.38	4.93	41.90			3	2	5	.16		.04			
675.8	677.9	72744	2.1	.0	2D9&	2.95	.27	1.57	4.11	25.80			3	2	5	.12		.04			

DDH: 75-05 UTM-N: 9495.1 UTM-E: 14907.1 UTM-ELEV: 4109.7 TOTAL DEPTH: 651.0 SECTION: 119+000
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

---DEPTHS---		-----ASSAYS-----																			
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
294.5	308.3	72785	13.8	.0	2D49	3.51	.20	3.90	8.43	54.20			7	11	19	.87		.12			
327.0	333.5	72787	6.5	.0	2D0	3.39	.23	2.44	5.51	41.80			7	10	17	.13		.05			
380.0	385.0	72789	5.0	.0	0Q9	3.11	.07	15.00	.32	246.90			4	9	14	.32		.04			
385.0	390.0	72790	5.0	.0	0Q9	3.34	.16	11.00	1.84	176.90			4	9	14	.28		.04			
390.0	395.0	72791	5.0	.0	2E14	3.26	.20	1.62	3.83	28.80			4	9	14	.21		.04			
395.0	400.0	72792	5.0	.0	2C35	3.50	.23	1.60	2.45	32.20			4	9	14	.18		.04			
400.0	405.0	72793	5.0	.0	2E19	3.48	.35	2.20	4.48	12.30			2	20	22	.17		.03			
405.0	410.0	72794	5.0	.0	2C39	3.55	.38	1.58	1.92	24.70			2	20	22	.19		.03			
410.0	415.0	72795	5.0	.0	2C35	3.31	.11	2.37	1.35	40.40			2	20	22	.19		.03			
415.0	420.0	72796	5.0	.0	2E19	3.95	.20	.38	1.16	12.30			2	20	22	.15		.03			
420.0	425.0	72797	5.0	.0	2E19	4.13	.34	.50	1.32	10.30			1	29	30	.16		.03			
425.0	430.0	72798	5.0	.0	2E19	4.02	.31	.34	.83	10.30			1	29	30	.15		.03			
430.0	435.0	72799	5.0	.0	2E19	3.88	.43	.06	.34	11.60			1	29	30	.16		.03			
435.0	440.0	72800	5.0	.0	2E19	4.05	.22	1.58	2.60	16.40			1	29	30	.18		.03			
440.0	445.0	72801	5.0	.0	2Q0	3.45	.48	1.10	1.17	27.40			5	10	15	.14		.06			
445.0	450.0	72802	5.0	.0	1D4	3.07	.34	1.57	.15	59.70			5	10	15	.20		.06			
450.0	455.0	72803	5.0	.0	1D4	3.19	.07	1.05	2.35	16.40			5	10	15	.21		.06			
455.0	460.0	72804	5.0	.0	1D4	3.33	.11	2.28	1.41	19.90			5	10	15	.20		.06			
460.0	465.0	72805	5.0	.0	2A43	3.52	.05	2.10	4.64	12.30			1	20	21	.20		.01			
465.0	470.0	72806	5.0	.0	2E41	4.05	.07	2.20	2.93	23.30			1	20	21	.19		.01			
470.0	475.0	72807	5.0	.0	2A43	3.62	.07	2.85	4.11	10.30			1	20	21	.18		.01			
475.0	480.0	72808	5.0	.0	2A43	3.61	.06	1.07	3.80	4.80			1	20	21	.20		.01			
480.0	485.0	72809	5.0	.0	2A43	3.50	.06	2.88	6.52	18.50			1	18	19	.20					
485.0	490.0	72810	5.0	.0	2A43	3.15	.06	2.14	7.25	6.90			1	18	19	.20					
490.0	495.0	72811	5.0	.0	2A43	3.28	.09	.97	4.95	8.90			1	18	19	.19					
495.0	500.0	72812	5.0	.0	2E15	3.45	.07	1.10	2.81				1	18	19	.20					
500.0	505.0	72813	5.0	.0	2A43	3.25	.08	2.28	5.22	11.60			1	16	17	.20					
505.0	510.0	72814	5.0	.0	2A43	3.12	.04	2.12	5.90	11.00			1	16	17	.23					
510.0	515.0	72815	5.0	.0	2A43	3.21	.11	3.00	6.88	16.40			1	16	17	.22					
515.0	520.0	72816	5.0	.0	2A43	3.22	.06	1.50	5.60				1	16	17	.21					
520.0	525.0	72817	5.0	.0	2A43	3.10	.05	1.65	4.20				1	16	17	.10		.02			
525.0	530.0	72818	5.0	.0	2A43	4.27	.10	1.76	6.32	11.00			1	16	17	.19		.02			
530.0	535.0	72819	5.0	.0	2A43	3.76	.05	3.62	4.82	8.20			1	16	17	.11		.02			
535.0	540.0	72820	5.0	.0	2A3	3.36	.05	.64	1.92	8.20			1	16	17	.13		.02			
540.0	545.0	72821	5.0	.0	2A3	3.82	.07	.81	1.61	14.40			1	16	17	.13		.02			
545.0	550.0	72822	5.0	.0	2A3	3.72	.05	.75	1.69	9.60			1	16	17	.17		.02			
550.0	555.0	72823	5.0	.0	2A3	3.65	.04	1.35	3.71	11.00			1	16	17	.12		.02			
555.0	560.0	72824	5.0	.0	2A3	3.64	.05	.65	1.47				1	16	17	.13		.02			
560.0	565.0	72825	5.0	.0	2A3	3.17	.03	.75	1.26	13.00			1	16	17	.16		.02			
565.0	570.0	72826	5.0	.0	2A3	3.70	.05	.45	1.66				1	16	17	.13		.02			
570.0	575.0	72827	5.0	.0	2D44	3.97	.08	2.82	11.40	19.20			1	16	17	.19		.02			
575.0	580.0	72828	5.0	.0	2C35	3.34	.15	.29	.99				1	16	17	.13		.02			
580.0	585.0	72829	5.0	.0	2A13	3.26	.03	.50	1.10	10.30			1	15	17	.18		.02			
585.0	590.0	72830	5.0	.0	2E0	3.66	.03	1.72	4.98	20.60			1	15	17	.19		.02			
590.0	595.0	72831	5.0	.0	2D4	3.80	.04	6.24	17.30	30.90			1	15	17	.17		.02			
595.0	600.0	72832	5.0	.0	2D4	4.20	.03	4.31	11.60	37.70			1	15	17	.18		.02			
600.0	605.0	72833	5.0	.0	2E4	4.78	.02	2.95	7.25	20.60			3	16	19	.15		.05			
605.0	610.0	72834	5.0	.0	2E4	3.83	.07	2.60	4.12	43.20			3	16	19	.17		.05			
610.0	615.0	72835	5.0	.0	2D4	3.19	.12	3.58	6.80	35.70			3	16	19	.19		.05			

DDH: 75-05 UTM-N: 9495.1 UTM-E: 14907.1 UTM-ELEV: 4109.7 TOTAL DEPTH: 651.0 SECTION: 119+000
RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

										-----ASSAYS-----											
---DEPTHS---		SAMPLE	INT.	REC.	ROCK	S.G.	Cu	Pb	Zn	Ag(AA)	Ag(FA)	Au(FA)	Po	Py	TOT	BaO	Hg	Mn	As	Ba	S.G.
FROM	TO	NO.			UNIT	PULP	%	%	%	g/mT	g/mT	g/mT	%	%	Fe	%	%	%	%	%	W.R.
615.0	617.0	72836	2.0	.0	2D0	3.03	.08	4.07	8.45	43.20				3	16	19	.18		.05		

DDH: 75-09 UTM-N: 9365.1 UTM-E: 14773.7 UTM-ELEV: 4063.7 TOTAL DEPTH: 723.0 SECTION: 119+000
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	ASSAYS														
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
327.0	329.0	72918	2.0	.0	2E4	4.50	.11	4.09	4.92	49.39			3	19	22	7.74		.31			
329.0	334.0	72919	5.0	.0	2G4	4.67	.19	8.25	6.86	108.40			3	19	22	31.49		.31			
334.0	339.0	72920	5.0	.0	2E2	4.63	.11	4.73	4.48	71.29			1	27	29	13.83		.07			
339.0	344.0	72921	5.0	.0	2G42	4.78	.05	3.31	5.87	46.60			1	27	29	7.20		.07			
344.0	349.0	72922	5.0	.0	2G42	4.80	.02	3.97	8.47	48.70			1	27	29	24.25		.07			
349.0	354.0	72923	5.0	.0	2G42	4.84	.11	2.91	6.00	47.29			1	27	29	8.15		.07			
354.0	359.0	72924	5.0	.0	2D0	3.64	.23	4.49	8.42	69.90			6	6	13	1.85		.05			
359.0	364.0	72925	5.0	.0	1D4	3.06	.08	2.50	5.91	50.10			6	6	13	.17		.05			
364.0	369.0	72926	5.0	.0	1D4	2.75	.07	.10	.29				6	6	13	.19		.05			
369.0	374.0	72927	5.0	.0	2D4&	3.29	.05	1.62	5.83	14.40			6	6	13	.08		.05			
374.0	379.0	72928	5.0	.0	2D4&	3.66	.07	2.04	6.04	29.49				30	31	.08		.02			
379.0	384.0	72929	5.0	.0	2E1	4.15	.28	2.02	3.52	21.19				30	31	.08		.02			
384.0	389.0	72930	5.0	.0	2E19	4.06	.24	.27	.72	8.19				30	31	.05		.02			
389.0	394.0	72931	5.0	.0	2E19	4.02	.40	.28	.39	18.50				30	31	.05		.02			
394.0	399.0	72932	5.0	.0	2C39	3.60	.17	.69	1.55	20.60			3	27	31	.07		.17			
399.0	404.0	72933	5.0	.0	2E1&	4.13	.11	.46	.63	1.39			3	27	31	.04		.17			
404.0	409.0	72934	5.0	.0	2E1&	3.97	.31	.19	.96	1.39			3	27	31	.04		.17			
409.0	414.0	72935	5.0	.0	2E89	4.46	.28	2.14	3.75	6.20			3	27	31	.04		.17			
414.0	419.0	72936	5.0	.0	2E09	4.42	.22	1.62	2.79	6.20			6	32	38	.02		.28			
419.0	424.0	72937	5.0	.0	2E89	4.15	.35	.91	1.06	5.50			6	32	38	.05		.28			
424.0	429.0	72938	5.0	.0	2E89	4.69	.26	1.31	2.06	6.20			6	32	38	.02		.28			
429.0	434.0	72939	5.0	.0	2E09	4.34	.23	.02	1.52	7.49			6	32	38	.02		.28			
434.0	439.0	72940	5.0	.0	2E1	3.81	.16	1.30	1.10	5.50			1	22	24	.04		.05			
439.0	444.0	72941	5.0	.0	2D45	3.87	.08	2.72	5.20				1	22	24	.07		.05			
444.0	449.0	72942	5.0	.0	2E1	3.97	.17	1.28	2.77	36.29			1	22	24	.05		.05			
449.0	454.0	72943	5.0	.0	2D4	3.43	.14	1.72	8.56	22.60			1	22	24	.07		.05			
454.0	459.0	72944	5.0	.0	2D4	3.70	.11	3.72	6.95	41.10			3	22	26	.07		.13			
459.0	464.0	72945	5.0	.0	2E1&	3.87	.29	.23	.95	3.39			3	22	26	.02		.13			
464.0	469.0	72946	5.0	.0	2F08	3.97	.16	1.39	6.94				3	22	26	.04		.13			
469.0	474.0	72947	5.0	.0	2E1	3.58	.14	.16	1.12	6.79			3	22	26	.05		.13			
474.0	479.0	72948	5.0	.0	2E1	3.49	.20	.23	1.06				3	26	29	.05		.17			
479.0	484.0	72949	5.0	.0	2E19	4.29	.29	.10	1.64	2.70			3	26	29	.04		.17			
484.0	489.0	72950	5.0	.0	2E19	4.02	.34	.11	.71				3	26	29	.02		.17			
489.0	494.0	72951	5.0	.0	2E19	4.37	.28	.08	1.30	2.70			3	26	29	.02		.17			
494.0	499.0	72952	5.0	.0	2E19	4.15	.34	.05	1.17	6.20			4	30	34	.04		.17			
499.0	504.0	72953	5.0	.0	2E19	4.08	.47	.41	.52	8.90			4	30	34	.04		.17			
504.0	509.0	72954	5.0	.0	2E19	3.91	.66	.51	1.33	4.09			4	30	34	.02		.17			
509.0	514.0	72955	5.0	.0	2E19	4.37	.62	.48	1.35				4	30	34	.02		.17			
514.0	519.0	72956	5.0	.0	2E19	4.08	.56	.57	2.68	13.69			2	31	34	.02		.08			
519.0	524.0	72957	5.0	.0	2E19	4.30	.14	.91	2.39	8.19			2	31	34	.11		.08			
524.0	529.0	72958	5.0	.0	2E19	4.29	.10	.29	1.56	7.49			1	32	34	.14		.01			
529.0	534.0	72959	5.0	.0	2E19	4.15	.10	.73	1.80	14.40			1	32	34	.14		.01			
534.0	539.0	72960	5.0	.0	2F4	4.21	.04	3.60	7.79	13.69				30	31	.14		.02			
539.0	544.0	72961	5.0	.0	2D4	5.04	.05	3.08	6.42	21.89				30	31	.13		.02			
544.0	549.0	72962	5.0	.0	2E4	3.37	.02	3.02	7.49	20.60				30	31	.14		.02			
549.0	554.0	72963	5.0	.0	2E4	4.61	.02	.91	3.58	9.59				30	31	.14		.02			
554.0	559.0	72964	5.0	.0	2D0	2.91	.13	.82	3.41	8.19			3	11	14	.23		.01			
559.0	564.0	72965	5.0	.0	2A13	3.06	.04	.90	2.37	6.20			3	11	14	.19		.01			
564.0	569.0	72966	5.0	.0	2A13	3.10	.04	.65	2.12	8.19			3	11	14	.17		.01			
569.0	574.0	72967	5.0	.0	2D0	3.22	.11	.90	3.58	15.80			3	11	14	.14		.01			
574.0	579.0	72968	5.0	.0	2A14	2.89	.05	1.89	4.44	29.39			1	7	9	.17		.02			

DDH: 75-09 UTM-N: 9365.1 UTM-E: 14773.7 UTM-ELEV: 4063.7 TOTAL DEPTH: 723.0 SECTION: 119+000
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

-----DEPTHS-----		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
579.0	584.0	72969	5.0	.0	2A14	3.29	.04	1.96	3.58	24.00			1	7	9	.17		.02			
584.0	589.0	72970	5.0	.0	2A0	2.93	.07	.86	2.64	15.09			1	7	9	.23		.02			
589.0	594.0	72971	5.0	.0	2A0	2.81	.05	.80	2.64	11.00			1	7	9	.23		.02			
594.0	599.0	72972	5.0	.0	2A0	2.93	.05	.40	1.69	11.00			1	6	7	.20		.02			
599.0	609.0	72973	10.0	.0	2A0	2.91	.05	.71	1.74	18.50			1	6	7	.20		.02			
609.0	614.0	72974	5.0	.0	2A0	2.87	.05	.59	2.02	13.69			1	6	7	.20		.02			
614.0	619.0	72975	5.0	.0	2A0	2.95	.05	.49	2.02	15.80			2	7	10	.22		.02			
619.0	624.0	72976	5.0	.0	2D0	3.00	.14	1.39	2.87	28.10			2	7	10	.20		.02			
624.0	629.0	72977	5.0	.0	2A0	3.00	.17	.28	1.06	11.59			2	7	10	.17		.02			
629.0	634.0	72978	5.0	.0	2A0	2.85	.05	.34	.34	18.50			2	7	10	.20		.02			
634.0	639.0	72979	5.0	.0	2A0	3.06	.08	1.64	1.28	20.60			12	2	14	.16		.04			
639.0	644.0	72980	5.0	.0	2C75	3.04	.20	.28	.62	12.30			12	2	14	.14		.04			
644.0	649.0	72981	5.0	.0	2C75	3.02	.16	1.69	2.27	21.89			12	2	14	.14		.04			
649.0	654.0	72982	5.0	.0	2A7	3.00	.13	1.52	3.00	15.09			12	2	14	.11		.04			
654.0	659.0	72983	5.0	.0	2A7	3.00	.17	.26	.07	11.00			10	1	12	.14		.02			
659.0	664.0	72984	5.0	.0	2C7	3.25	.17	3.10	6.25	34.29			10	1	12	.19		.02			
664.0	669.0	72985	5.0	.0	1D21	2.79	.10	1.04	.67	28.80			10	1	12	.23		.02			
669.0	674.0	72986	5.0	.0	1D21	2.89	.10	.24	.80	9.59			10	1	12	.23		.02			
674.0	679.0	72987	5.0	.0	1D21	2.91	.08	1.01	1.82	17.80			4	3	7	.20		.01			
679.0	684.0	72988	5.0	.0	2A0	2.91	.08	1.35	1.37	17.10			4	3	7	.14		.01			
684.0	689.0	72989	5.0	.0	2L0	2.85	.11	.62	1.78	10.30			4	3	7	.14		.01			
689.0	694.0	72990	5.0	.0	2D0&	2.93	.08	3.02	4.20	67.50			4	3	7	.11		.01			
694.0	699.0	72991	5.0	.0	2D0&	3.00	.13	2.47	3.16	38.39			3	3	6	.08					
699.0	704.0	72992	5.0	.0	1D4	2.91	.05	3.37	5.05	40.50			3	3	6	.13					
704.0	709.0	72993	5.0	.0	2A0	2.85	.02	1.03	1.87	14.40			3	3	6	.16					

DDH: 75-10 UTM-N: 9302.4 UTM-E: 15100.8 UTM-ELEV: 4141.0 TOTAL DEPTH: 957.0 SECTION: 121+000
 RFE: 52 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

---DEPTHS---						----- ASSAYS -----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
485.0	490.0	72996	5.0	.0	2D35	3.31	.05	1.73	4.62	13.00			2	14	17	.11		.01			
490.0	495.0	72997	5.0	.0	2D35	3.35	.05	1.39	3.72	8.19			1	22	24	.11		.01			
495.0	500.0	72998	5.0	.0	2D35	3.37	.04	1.43	3.72	26.69			1	16	18	.11		.02			
500.0	505.0	72999	5.0	.0	2D35	3.35	.07	1.05	4.21	15.09			1	16	18	.11		.02			
505.0	510.0	73000	5.0	.0	2D35	2.91	.04	1.69	5.20	7.49			1	16	18	.10		.02			
510.0	515.0	73001	5.0	.0	2D35	4.09	.02	1.87	3.29	21.30				16	17	.11		.01			
515.0	520.0	73002	5.0	.0	2D35	3.02	.05	1.85	5.19	10.30				16	17	.11		.01			
520.0	525.0	73003	5.0	.0	2C35	3.12	.14	.35	1.10	8.90				16	17	.11		.01			
525.0	530.0	73004	5.0	.0	2C35	3.10	.08	.83	2.83	3.39				16	17	.08		.01			
530.0	535.0	73005	5.0	.0	2D35	3.41	.10	2.70	4.54	49.39				19	20	.05		.02			
535.0	540.0	73006	5.0	.0	2C35	4.06	.16	1.36	.75	21.89				19	20	.04		.02			
540.0	545.0	73007	5.0	.0	2E19	3.56	.24	.62	1.79	4.09				19	20	.04		.02			
545.0	550.0	73008	5.0	.0	2E11	3.66	.11	.31	.92	4.09				19	20	.08		.02			
550.0	555.0	73009	5.0	.0	2C35	3.62	.05	.55	1.71	9.59			1	17	18	.08		.02			
555.0	560.0	73010	5.0	.0	2C35	3.29	.05	.61	1.46	15.09			1	17	18	.13		.02			
560.0	565.0	73011	5.0	.0	2C35	3.25	.05	1.71	1.96	20.60			1	17	18	.14		.02			
565.0	570.0	73012	5.0	.0	2C35	3.25	.04	1.59	2.24	5.50			1	17	18	.16		.02			
570.0	575.0	73013	5.0	.0	2C35	3.41	.05	1.11	2.10	5.50			1	14	16	.17		.02			
575.0	580.0	73014	5.0	.0	2D51	3.35	.05	1.64	1.53	5.50			1	14	16	.14		.02			
580.0	585.0	73015	5.0	.0	2D5	3.33	.08	1.77	7.92	10.30			1	14	16	.17		.02			
585.0	590.0	73016	5.0	.0	2C35	3.27	.05	.65	2.14	9.59			1	14	16	.05		.02			
590.0	595.0	73017	5.0	.0	2C35	3.68	.08	1.04	2.37	13.69			1	20	21	.08		.02			
595.0	600.0	73018	5.0	.0	2D35	3.56	.05	3.60	7.20	20.60			1	20	21	.14		.02			
600.0	605.0	73019	5.0	.0	2C35	3.49	.04	.75	2.31	25.69			1	20	21	.11		.02			
605.0	610.0	73020	5.0	.0	2E05	3.47	.02	1.07	1.81	36.70			1	20	21	.05		.02			
610.0	613.5	73021	3.5	.0	2D4	4.05	.05	3.68	10.59	363.50			2	16	19	.07		.02			
624.5	630.0	73023	5.5	.0	2D05	3.25	.11	1.55	3.58	122.79			2	16	19	.14		.02			
630.0	635.0	73024	5.0	.0	1D40	2.99	.08	2.54	3.18	110.40			3	3	7	.14		.05			
635.0	638.0	73025	3.0	.0	2B4	3.18	.14	1.65	4.98	24.00			3	3	7	.11		.05			

DDH: 75-11 UTM-N: 8878.3 UTM-E: 14097.0 UTM-ELEV: 4000.1 TOTAL DEPTH: 2120.0 SECTION: 118+000
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

-----DEPTHS-----						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
477.0	480.0	73030	3.0	.0	2A0	2.95	.16	.40	.75				3	7	10	.16		.02			
480.0	485.0	73031	5.0	.0	2A4	3.04	.08	1.49	2.60	8.19			3	7	10	.10		.02			
485.0	490.0	73032	5.0	.0	2A4	2.60	.05	2.50	5.33	24.00			3	7	10	.14		.02			
490.0	495.0	73033	5.0	.0	2A4	2.81	.15	1.60	2.93	6.20			11	11	22	.26		.02			
495.0	500.0	73034	5.0	.0	2F4&	3.87	.17	3.60	6.29	33.60			11	11	22	.17		.02			
500.0	505.0	73035	5.0	.0	2F4&	4.30	.31	5.50	7.08	41.79			11	11	22	.08		.02			
505.0	510.0	73036	5.0	.0	2H49	3.50	.35	4.02	5.78	35.00			11	11	22	.39		.02			
510.0	515.0	73037	5.0	.0	10E0	2.73	.01	.10	.08	4.79			22	5	27	.85		.01			
515.0	520.0	73038	5.0	.0	2H48	3.81	.32	5.19	7.89	55.49			22	5	27	.23		.10			
520.0	525.0	73039	5.0	.0	2H48	5.21	.44	6.84	9.59	41.79			22	5	27	.40		.10			
525.0	530.0	73040	5.0	.0	2H48	3.89	.34	6.61	9.69	68.59			22	5	27	.46		.10			
530.0	535.0	73041	5.0	.0	2H48	3.79	.44	5.50	7.58	68.59			12	21	33	.40		.10			
535.0	540.0	73042	5.0	.0	2F4	4.25	.32	5.58	8.98	61.70			12	21	33	.17		.10			
540.0	545.0	73043	5.0	.0	2F4	4.62	.08	4.90	8.10	54.89			12	21	33	.11		.10			
545.0	550.0	73044	5.0	.0	2F4	4.00	.11	4.96	7.78	60.39			12	21	33	.08		.10			
550.0	555.0	73045	5.0	.0	2H48	4.17	.64	4.98	7.17	58.29			21	7	28	.41		.08			
555.0	560.0	73046	5.0	.0	2D79	3.31	.23	2.02	5.23	35.00			21	7	28	.14		.08			
560.0	565.0	73047	5.0	.0	2H49	3.60	.61	4.09	7.09	76.09			21	7	28	.10		.08			
565.0	570.0	73048	5.0	.0	2H49	3.79	.49	3.89	4.59	96.70			21	7	28	1.74		.08			

DDH: 75001 UTM-N: 9431.1 UTM-E: 14149.0 UTM-ELEV: 3832.3 TOTAL DEPTH: 233.0 SECTION:
 RFE: RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	ASSAYS														
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
39.0	42.0	72643	3.0	.0	****	3.00	.28	5.93	6.61	118.60			8	12	21	.02		.07			
42.0	47.0	72644	5.0	.0	****	2.96	.38	1.60	2.87	19.20			8	12	21	.02		.07			
47.0	52.0	72645	5.0	.0	****	2.96	.22	1.27	1.52	13.70			8	12	21	.03		.07			
52.0	57.0	72646	5.0	.0	****	3.26	.45	.08	.12				8	12	21	.02		.07			
57.0	62.0	72647	5.0	.0	****	3.23	.41	.37	.38	1.70			8	12	21	.03		.07			
62.0	67.0	72648	5.0	.0	****	3.51	.29	.31	.56	1.40			10	13	23	.02		.11			
67.0	72.0	72649	5.0	.0	****	3.17	.27	.02	.16				10	13	23	.02		.11			
72.0	77.0	72650	5.0	.0	****	3.05	.24	.10	.13				10	13	23	.16		.11			
77.0	82.0	72651	5.0	.0	****	3.67	.28	2.48	2.60	21.20			10	13	23	3.79		.11			
82.0	87.0	72652	5.0	.0	****	4.15	.40	5.01	7.00	92.60			10	21	31	.18		.32			
87.0	92.0	72653	5.0	.0	****	4.59	.18	4.93	6.30	113.80			10	21	31	3.43		.32			
92.0	97.0	72654	5.0	.0	****	4.60	.15	7.39	6.40	87.80			10	21	31	16.17		.32			
97.0	102.0	72655	5.0	.0	****	4.46	.23	5.71	6.00	87.10			10	21	31	8.67		.32			
102.0	107.0	72656	5.0	.0	****	4.62	.13	5.24	5.25	53.50			1	33	35	20.49		.06			
107.0	112.0	72657	5.0	.0	****	4.71	.16	3.30	5.48	43.90			1	33	35	.20		.06			
112.0	117.0	72658	5.0	.0	****	4.14	.14	1.77	2.00	32.20			1	33	35	.04		.06			
117.0	122.0	72659	5.0	.0	****	4.63	.30	2.23	1.70	24.70			1	33	35	.02		.06			
122.0	127.0	72660	5.0	.0	****	4.71	.33	2.54	2.89	17.10			4	33	38	.01		.17			
127.0	132.0	72661	5.0	.0	****	4.51	.49	1.86	2.94	28.10			4	33	38	.02		.17			
132.0	137.0	72662	5.0	.0	****	4.78	.26	3.98	3.78	43.90			4	33	38	1.78		.17			
137.0	142.0	72663	5.0	.0	****	4.45	.20	2.63	2.73	34.30			4	33	38	4.13		.17			
142.0	147.0	72664	5.0	.0	****	4.02	.17	1.31	1.30	10.30			3	31	34	.03		.10			
147.0	152.0	72665	5.0	.0	****	4.28	.11	1.95	2.32	12.30			3	31	34	.02		.10			
152.0	157.0	72666	5.0	.0	****	4.36	.21	3.05	3.25	27.40			3	31	34	5.11		.10			
157.0	162.0	72667	5.0	.0	****	4.65	.27	4.80	4.98	61.70			3	31	34	4.64		.10			
162.0	167.0	72668	5.0	.0	****	4.58	.20	3.35	4.13	24.70			4	34	38	.05		.14			
167.0	172.0	72669	5.0	.0	****	4.61	.19	6.39	11.30	30.90			4	34	38	.05		.14			
172.0	177.0	72670	5.0	.0	****	4.61	.69	.56	1.52	12.30			4	34	38	.02		.14			
177.0	182.0	72671	5.0	.0	****	4.71	.40	2.30	3.60	9.60			4	34	38	.01		.14			
182.0	187.0	72672	5.0	.0	****	4.52	.68	1.58	2.40	13.00			2	35	37	.01		.05			
187.0	192.0	72673	5.0	.0	****	4.69	.34	2.42	4.94	12.30			2	35	37	.02		.05			
192.0	197.0	72674	5.0	.0	****	4.12	.57	4.44	3.44	31.50			2	35	37	.05		.05			
197.0	202.0	72675	5.0	.0	****	4.74	.17	3.90	7.20	26.70			2	35	37	.03		.05			
202.0	207.0	72676	5.0	.0	****	4.61	.33	4.63	6.52	25.40			1	33	34	.02		.03			
207.0	212.0	72677	5.0	.0	****	4.55	.30	2.75	3.58	21.90			1	33	34	.03		.03			
212.0	217.0	72678	5.0	.0	****	4.11	.36	3.17	4.78	25.40			1	33	34	.05		.03			
217.0	222.0	72679	5.0	.0	****	4.32	.20	2.72	7.40	18.50			1	33	34	.04		.03			
222.0	227.0	72680	5.0	.0	****	2.77	.07	1.25	3.10	17.10			2	5	7	.07		.02			
227.0	233.0	72681	6.0	.0	****	2.75	.14	1.28	2.43	35.00			2	5	7	.07		.02			

DDH: 75002 UTM-N: 8997.7 UTM-E: 14399.9 UTM-ELEV: 4025.5 TOTAL DEPTH: 687.0 SECTION: 119+000
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

---DEPTHS---		SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	ASSAYS														
FROM	TO					Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
513.5	515.0	72684	1.5	.0 2H49	4.33	.68	5.74	7.65	91.20			9	25	35	.30		.29			
515.0	520.0	72685	5.0	.0 2F4	4.70	.17	6.60	7.24	96.00			9	25	35	.02		.29			
520.0	525.0	72686	5.0	.0 2F4	5.63	.08	5.98	7.44	71.30			9	25	35	.99		.29			
525.0	530.0	72687	5.0	.0 2H469	4.44	.36	5.60	7.21	58.30			9	25	35	2.03		.29			
530.0	535.0	72688	5.0	.0 2E4(2	4.79	.31	4.57	6.58	50.10			16	21	38	1.00		.25			
535.0	540.0	72689	5.0	.0 2F467	4.60	.11	5.66	6.30	69.30			16	21	38	5.64		.25			
540.0	545.0	72690	5.0	.0 2H49	4.50	.41	4.86	5.80	54.90			16	21	38	.39		.25			
545.0	550.0	72691	5.0	.0 2H49(	5.80	.35	5.42	7.10	59.00			16	21	38	1.84		.25			
550.0	555.0	72692	5.0	.0 2H49(	5.76	.36	5.94	6.36	78.90			13	24	38	5.30		.42			
555.0	560.0	72693	5.0	.0 2H496	4.39	.65	4.44	4.49	52.10			13	24	38	1.08		.42			
560.0	565.0	72694	5.0	.0 2E489	4.55	.24	3.72	4.15	37.00			13	24	38	.66		.42			
565.0	570.0	72695	5.0	.0 2E49	4.59	.28	3.14	3.00	42.50			13	24	38	.74		.42			
570.0	575.0	72696	5.0	.0 2F69(	4.76	.33	3.52	3.47	58.30			13	24	38	1.28		.42			
575.0	580.0	72697	5.0	.0 2D9(2	3.88	.43	3.16	3.12	48.00			3	29	32	3.17		.11			
580.0	585.0	72698	5.0	.0 2F0	4.61	.09	4.23	5.02	44.60			3	29	32	.15		.11			
585.0	590.0	72699	5.0	.0 2G4	5.36	.19	5.64	6.38	52.80			3	29	32	17.16		.11			
590.0	595.0	72700	5.0	.0 2E0	4.71	.10	2.42	1.40	15.80			3	29	32	.05		.11			
595.0	600.0	72701	5.0	.0 2E9	4.73	.31	2.44	1.85	15.80			11	17	29	.05		.10			
600.0	605.0	72702	5.0	.0 2D9	3.41	.41	1.42	3.90	17.80			11	17	29	.08		.10			
605.0	610.0	72703	5.0	.0 2H09	3.25	.62	1.90	3.40	25.40			11	17	29	.21		.10			
610.0	615.0	72704	5.0	.0 2D459	4.40	.28	3.10	7.12	47.30			11	17	29	.12		.10			
615.0	620.0	72705	5.0	.0 2A0	2.76	.04	.81	2.56	10.30			3	20	23	.22		.02			
620.0	625.0	72706	5.0	.0 2E4	4.03	.03	2.42	7.70	26.10			3	20	23	.09		.02			
625.0	630.0	72707	5.0	.0 2E4	5.55	.04	1.81	6.54	8.20			3	20	23	.10		.02			
630.0	635.0	72708	5.0	.0 2E4	3.86	.15	3.46	6.40	22.60			3	20	23	.10		.02			
635.0	640.0	72709	5.0	.0 2D459	2.90	.22	.40	7.25	11.00			12	2	14	.14		.03			
640.0	645.0	72710	5.0	.0 2A4	2.67	.11	.81	3.32	16.40			12	2	14	.14		.03			
645.0	650.0	72711	5.0	.0 2A4	2.70	.10	1.27	3.10	17.10			12	2	14	.14		.03			
650.0	654.7	72712	4.7	.0 2A49	3.83	1.11	2.12	4.25	56.90			12	2	14	.06		.03			

DDH: 75007 UTM-N: 9856.4 UTM-E: 14432.6 UTM-ELEV: 3906.0 TOTAL DEPTH: 261.0 SECTION:
 RFE: RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %
49.0	50.0	72842	1.0	.0	****	3.56	.24	.20	.05	11.00			2	22	24	.03		.02		
50.0	55.0	72843	5.0	.0	****	3.36	.12	.18	.96	2.00			2	22	24	.04		.02		
55.0	60.0	72844	5.0	.0	****	3.58	.17	.76	2.20	2.00			1	26	28	.02		.02		
60.0	65.0	72845	5.0	.0	****	3.66	.06	4.55	3.71	87.80			1	26	28	.03		.02		
65.0	70.0	72846	5.0	.0	****	4.03	.04	2.23	4.62	8.90			1	26	28	.03		.02		
70.0	75.0	72847	5.0	.0	****	3.64	.04	1.94	4.00	8.90			1	26	28	.05		.02		
75.0	80.0	72848	5.0	.0	****	3.73	.04	1.12	3.00	8.90			1	22	24	.04		.01		
80.0	85.0	72849	5.0	.0	****	3.49	.05	1.76	4.14	11.00			1	22	24	.08		.01		
85.0	90.0	72850	5.0	.0	****	3.51	.06	1.78	4.38	17.10			1	22	24	.04		.01		
90.0	95.0	72851	5.0	.0	****	3.50	.04	1.50	4.85	13.70			1	22	24	.06		.01		
95.0	100.0	72852	5.0	.0	****	3.41	.03	.25	1.49	4.80			2	17	19	.06		.02		
100.0	105.0	72853	5.0	.0	****	3.46	.05	3.76	4.20	30.90			2	17	19	.06		.02		
105.0	110.0	72854	5.0	.0	****	3.22	.03	1.12	4.73	17.10			2	17	19	.07		.02		
110.0	115.0	72855	5.0	.0	****	3.27	.03	1.50	4.53	17.10			2	17	19	.06		.02		
115.0	120.0	72856	5.0	.0	****	3.44	.04	.23	1.48	6.80			1	19	21	.08		.01		
120.0	125.0	72857	5.0	.0	****	3.43	.07	1.30	5.16	17.10			1	19	21	.05		.01		
125.0	130.0	72858	5.0	.0	****	3.36	.05	1.88	6.58	11.00			1	19	21	.08		.01		
130.0	135.0	72859	5.0	.0	****	3.44	.02	.26	.53	8.90			1	19	21	.07		.01		
135.0	140.0	72860	5.0	.0	****	3.37	.04	1.88	4.05	21.20			1	18	19	.11		.01		
140.0	145.0	72861	5.0	.0	****	3.44	.03	1.01	1.16	13.70			1	18	19	.08		.01		
145.0	150.0	72862	5.0	.0	****	3.53	.05	.72	.91	8.20			1	18	19	.06		.01		
150.0	155.0	72863	5.0	.0	****	3.27	.04	3.09	3.22	37.70			1	18	19	.08		.01		
155.0	160.0	72864	5.0	.0	****	3.39	.03	.33	1.18	10.30			1	15	17	.08		.01		
160.0	165.0	72865	5.0	.0	****	3.25	.04	1.50	2.78	3.40				15	15	.06		.01		
165.0	170.0	72866	5.0	.0	****	3.22	.06	.67	4.50	15.40				15	15	.08		.01		
170.0	175.0	72867	5.0	.0	****	3.31	.04	.42	1.93	8.90			1	15	17	.03		.01		
175.0	180.0	72868	5.0	.0	****	3.29	.07	1.74	3.21	12.30			2	17	19	.07		.01		
180.0	185.0	72869	5.0	.0	****	3.12	.06	1.87	4.48	21.90			2	17	19	.09		.01		
185.0	190.0	72870	5.0	.0	****	2.87	.04	1.35	2.10	22.60			2	17	19	.06		.01		
190.0	195.0	72871	5.0	.0	****	4.02	.02	6.02	12.60	47.30			2	17	19	.02		.01		
195.0	200.0	72872	5.0	.0	****	4.72	.02	6.05	12.20	51.40			1	36	38	.01		.01		
200.0	205.0	72873	5.0	.0	****	4.76	.01	1.91	6.38	28.80			1	36	38			.01		
205.0	210.0	72874	5.0	.0	****	4.79	.02	1.20	6.25	15.10			1	36	38	.02		.01		
210.0	215.0	72875	5.0	.0	****	4.85	.02	3.53	7.31	32.90			1	36	38	.01		.01		
215.0	220.0	72876	5.0	.0	****	4.67	.03	7.45	17.20	63.80			3	14	17			.04		
220.0	225.0	72877	5.0	.0	****	3.22	.24	.67	5.27	10.30			3	14	17	.05		.04		
225.0	230.0	72878	5.0	.0	****	3.14	.10	.50	2.00	14.40			3	14	17	.04		.04		
230.0	235.0	72879	5.0	.0	****	2.89	.15	.35	.44	8.60			3	14	17	.09		.04		
235.0	240.0	72880	5.0	.0	****	2.84	.09	.76	.82	16.10			3	4	8	.12		.05		
240.0	245.0	72881	5.0	.0	****	2.79	.07	.35	.07	3.40			3	4	8	.08		.05		
245.0	250.0	72882	5.0	.0	****	2.99	.18	.45	2.27	5.10			3	4	8	.06		.05		
250.0	255.0	72883	5.0	.0	****	3.05	.19	1.12	3.70	19.50			3	4	8	.07		.05		
255.0	261.0	72884	6.0	.0	****	3.18	.15	2.52	5.18	39.10			3	4	8	.04		.05		

PAGE: 100

[illegible]

PAGE : 101

[illegible]

PAGE : 102

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %
720.0	724.5	04244	4.5	.0	2H4	.22	5.03	8.13	85.00			.20								
724.5	729.5	04245	5.0	.0	1D/2H	.07	4.20	.19	263.70											
729.5	734.0	04246	4.5	.0	2C0	.08	.68	1.91	30.19											
734.0	739.0	04247	5.0	.0	2D0	.10	1.96	3.35	47.29											
739.0	743.0	04248	4.0	.0	2E4	.28	4.95	7.61	100.09			.20								
743.0	748.0	04249	5.0	.0	2B4	.08	1.64	3.41	28.49											
748.0	753.0	04250	5.0	.0	2L1	.05	.02	.02	.29											
753.0	758.0	04501	5.0	.0	1D0	.02	.01	.01	.29											
758.0	762.5	04502	4.5	.0	1D0	.05	.48	.01	27.10											
762.5	766.5	04503	4.0	.0	1D0	.08	.08	.01	.10											
766.5	771.5	04504	5.0	.0	2H4	.41	5.25	6.44	134.09			.20								

DDH: 76-01 UTM-N: 9067.7 UTM-E: 15135.1 UTM-ELEV: 4185.6 TOTAL DEPTH: 754.0 SECTION: 122+020
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														S.G. W.R.
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	
607.4	609.0	73057	1.6	.0	2C9	2.99	.41	1.02	2.72	24.30				6 12	18	.16		.10			
609.0	611.0	73058	2.0	.0	2C9	3.41	.59	.80	.46	27.39				6 12	18	.08		.10			
611.0	613.0	73059	2.0	.0	2D39	3.33	.41	3.49	1.38	52.10				6 12	18	.08		.10			
613.0	614.2	73060	1.2	.0	2D39	3.08	.29	2.02	3.16	21.60				6 12	18	.11		.10			
614.2	614.8	73061	.6	.0	2D3	3.47	.14	1.43	3.58	8.19				6 12	18	.10		.10			
614.8	616.0	73062	1.2	.0	2D3	3.91	.05	8.16	18.10	32.60				6 12	18	.14		.10			
616.0	616.5	73063	.5	.0	2D3	3.75	.17	3.47	2.85	17.80				6 12	18	.05		.10			
616.5	616.8	73064	.3	.0	1E19	2.99	.10	.29	.23	8.19				6 12	18	.35		.10			
616.8	617.2	73065	.4	.0	1E19	2.98	.13	.39	.10	8.90				6 12	18	.22		.10			
617.2	617.4	73066	.2	.0	2D39	4.46	.07	8.65	9.16	39.79				6 12	18	.08		.10			
617.4	618.3	73067	.9	.0	2D3	3.81	.23	8.04	10.90	41.79				6 12	18	.08		.10			
618.3	618.9	73068	.6	.0	2D3	3.54	.13	2.73	4.05	21.19				6 12	18	.08		.10			
618.9	619.6	73069	.7	.0	2C0	3.37	.14	.35	.27	16.39				6 12	18	.08		.10			
619.6	619.9	73070	.3	.0	1D4	2.91	.04	.14	.23					2 16	19	.14		.02			
619.9	621.0	73071	1.1	.0	1D4	2.87	.02	.11	.19					2 16	19	.16		.02			
621.0	621.7	73072	.7	.0	1D4	3.29	.10	.16	.38	7.90				2 16	19	.13		.02			
621.7	623.0	73073	1.3	.0	2C0	3.49	.10	.99	1.96	12.30				2 16	19	.10		.02			
623.0	623.5	73074	.5	.0	2D35	3.47	.04	1.17	3.29	8.59				2 16	19	.13		.02			
623.5	626.4	73075	2.9	.0	2D35	3.47	.05	2.41	3.37	11.59				2 16	19	.11		.02			
626.4	631.4	73076	5.0	.0	2C53	3.62	.11	.99	2.17					2 16	19	.08		.02			
631.4	636.4	73077	5.0	.0	2D35	3.43	.05	1.74	5.96	9.59				2 16	19	.11		.02			
636.4	639.4	73078	3.0	.0	2D35	3.54	.05	1.99	5.94	10.30				2 16	19	.11		.02			
639.4	640.7	73079	1.3	.0	2C35	3.39	.04	.93	2.35					2 16	19	.11		.02			
640.7	645.7	73080	5.0	.0	2D35	3.37	.11	1.37	2.60	15.80				2 20	22	.11		.02			
645.7	650.7	73081	5.0	.0	2C35	3.47	.07	.47	3.20					2 20	22	.13		.02			
650.7	655.7	73082	5.0	.0	2C35	3.68	.10	.61	1.34					2 20	22	.10		.02			
655.7	660.0	73083	4.3	.0	2C3	3.85	.13	.54	1.35	4.79				2 20	22	.05		.02			
660.0	661.0	73084	1.0	.0	2C3	3.87	.08	.08	.69	6.79				2 20	22	.08		.02			
661.0	665.0	73085	4.0	.0	2C3	4.15	.29	.44	1.39	3.39				3 24	27	.05		.02			
665.0	666.0	73086	1.0	.0	2E4	4.33	.17	1.95	5.48					3 24	27	.02		.02			
666.0	669.0	73087	3.0	.0	2C3	3.89	.11	.41	.62	7.49				3 24	27	.05		.02			
669.0	671.0	73088	2.0	.0	2A3E	3.47	.04	1.28	1.60	8.19				3 24	27	.17		.02			

DDH: 76-02 UTM-N: 8892.2 UTM-E: 15099.2 UTM-ELEV: 4181.5 TOTAL DEPTH: 821.0 SECTION: 123+015
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	---ASSAYS---													
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %
582.7	583.7	73094	1.0	.0	2D49	3.47	.28	2.93	8.30	47.29			4	13	18	.46		.17		
583.7	586.5	73095	2.8	.0	2G4	4.54	.02	2.89	6.13	120.29			4	13	18	39.25		.17		
586.5	591.5	73096	5.0	.0	2G40	4.55	.10	6.29	5.70	66.20			4	13	18	32.95		.17		
591.5	596.5	73097	5.0	.0	2G40	4.50	.14	3.74	3.14	88.79			3	21	25	13.00		.16		
596.5	601.5	73098	5.0	.0	2G40	4.84	.11	6.04	6.75	81.90			3	21	25	25.67		.16		
601.5	606.5	73099	5.0	.0	2G40	4.63	.14	6.63	7.26	46.60			3	21	25	28.19		.16		
606.5	611.5	73100	5.0	.0	2G40	4.61	.10	4.25	7.58	13.69			3	21	25	12.60		.16		
611.5	616.5	73101	5.0	.0	2C30	4.16	.05	.83	1.26	40.79			2	30	32	.08		.02		
616.5	621.2	73102	4.7	.0	2C3	3.74	.05	.58	.29	20.19			2	30	32	.19		.02		
621.2	626.3	73103	5.1	.0	2E40	4.59	.32	4.54	4.34	18.19			2	30	32	.19		.02		
626.3	630.0	73104	3.7	.0	2E19	3.95	.23	1.52	.77	40.79			2	30	32	.17		.02		
630.0	631.5	73105	1.5	.0	2E41	4.50	.10	5.13	4.90	27.10			2	30	32	.02		.02		
631.5	639.8	73106	8.3	.0	2E40	4.36	.07	2.64	5.65	60.29			12	22	34	.75		.07		
639.8	640.5	73107	.7	.0	2H4	3.95	.17	3.89	8.65	76.79			12	22	34	.63		.07		
640.5	641.5	73108	1.0	.0	2D49	3.35	.29	3.97	13.00	69.29			12	22	34	.61		.07		
641.5	643.8	73109	2.3	.0	2H49	4.40	.46	4.59	7.70	63.10			12	22	34	2.79		.07		
643.8	646.5	73110	2.7	.0	2E40	4.44	.02	3.10	5.54	34.79			12	22	34	3.76		.07		
646.5	648.0	73111	1.5	.0	2E49	4.33	.35	2.24	4.95	30.19			12	22	34	4.54		.07		
648.0	651.4	73112	3.4	.0	2H39	3.79	.40	.63	1.99	14.40			12	22	34	.31		.07		
651.4	656.5	73113	5.1	.0	2E19	4.17	.39	.27	.69	13.69			2	30	32	.02		.02		
656.5	661.5	73114	5.0	.0	2E19	4.30	.56	.90	1.37	20.89			2	30	32	.01		.02		
661.5	665.5	73115	4.0	.0	2C9	3.64	.28	.16	.78	10.59			2	30	32	.04		.02		
665.5	671.5	73116	6.0	.0	2C0	3.81	.08	.56	.97	16.39			2	30	32	.04		.02		
671.5	676.5	73117	5.0	.0	2E9&	4.29	.28	.28	1.23	7.49			2	33	35	.02		.02		
676.5	677.7	73118	1.2	.0	2E9&	4.46	.27	.05	.94	7.49			2	33	35	.02		.02		
677.7	682.0	73119	4.3	.0	2C50	4.30	.11	.45	1.99	8.19			2	33	35	.02		.02		
682.0	686.5	73120	4.5	.0	2C0	3.64	.08	.14	1.69	7.49			2	33	35	.08		.02		
686.5	691.5	73121	5.0	.0	2C9	4.84	.59	.90	1.67				2	33	35	.05		.02		
691.5	696.5	73122	5.0	.0	2C9	4.65	.52	.90	1.35	12.00			3	30	34	.02		.08		
696.5	701.5	73123	5.0	.0	2C90	4.84	.48	1.08	1.64	13.69			3	30	34	.01		.08		
701.5	706.5	73124	5.0	.0	2C9	4.37	.40	2.16	1.57	22.60			3	30	34	.05		.08		
706.5	709.0	73125	2.5	.0	2C9	3.87	.48	1.16	.84	11.59			3	30	34	.04		.08		
709.0	711.5	73126	2.5	.0	2E89	4.90	.32	.54	1.77	6.90			3	30	34	.02		.08		
711.5	715.1	73127	3.6	.0	2E48	4.42	.17	3.58	3.70	23.30			10	23	33	.02		.20		
715.1	716.5	73128	1.4	.0	2E31	3.91	.28	.49	1.83	11.00			10	23	33	.02		.20		
716.5	721.5	73129	5.0	.0	2E31	3.68	.41	.20	.99	9.90			10	23	33	.02		.20		
721.5	726.8	73130	5.3	.0	2C30	4.17	.14	2.45	1.46	17.10			10	23	33	.02		.20		
726.8	731.5	73131	4.7	.0	2E39	3.66	.20	.14	.34	1.39			10	23	33	.02		.20		
731.5	735.2	73132	3.7	.0	2E39	3.54	.23	.51	1.94	12.69			7	19	27	.07		.17		
735.2	736.5	73133	1.3	.0	2D0	3.58	.07	3.00	4.58	40.79			7	19	27	.10		.17		
736.5	742.0	73134	5.5	.0	2C90	3.50	.24	.68	2.89	27.39			7	19	27	.08		.17		
742.0	747.1	73135	5.1	.0	2C9	3.76	.20	.40	1.32				7	19	27	.02		.17		
747.1	751.5	73136	4.4	.0	2E89	4.15	.89	.17	1.08	6.79			7	19	27	.01		.17		
751.5	756.5	73137	5.0	.0	2C90	4.01	.31	.11	1.03	22.60			6	26	32	.01		.13		
756.5	761.5	73138	5.0	.0	2C90	4.26	.34	.28	.28				6	26	32	.01		.13		
761.5	766.5	73139	5.0	.0	2E89	4.34	.62	.28	.41	57.20			6	26	32	.01		.13		
766.5	771.5	73140	5.0	.0	2E89	4.50	.61	.23	.52	3.39			6	26	32	.02		.13		
771.5	776.5	73141	5.0	.0	2C39	4.69	.40	2.35	3.74	6.79			6	29	35	.01		.14		
776.5	781.5	73142	5.0	.0	2E89	4.74	.26	1.78	2.75	40.79			6	29	35	.01		.14		
781.5	786.5	73143	5.0	.0	2E89	4.46	.59	.56	1.73	11.40			6	29	35	.02		.14		
786.5	791.5	73144	5.0	.0	2E89	4.21	.39	.48	1.20				6	29	35	.05		.14		

DDH: 76-02 UTM-N: 8892.2 UTM-E: 15099.2 UTM-ELEV: 4181.5 TOTAL DEPTH: 821.0 SECTION: 123+015
RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

-----DEPTHS-----		-----ASSAYS-----																		
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
791.5	792.7	73145	1.2	.0	2E8&	4.05	.13	.75	1.18			5	8	13	.02		.05			
792.7	793.4	73146	.7	.0	2D4	3.41	.17	4.26	11.69	26.39		5	8	13	.01		.05			
793.4	796.5	73147	3.1	.0	2B0	2.95	.14	.68	.94	58.20		5	8	13	.10		.05			
796.5	801.5	73148	5.0	.0	2B00	3.37	.20	5.15	1.63	238.99		5	8	13	.05		.05			
801.5	805.5	73149	4.0	.0	2C00	3.06	.13	2.39	5.29	14.40		5	8	13	.10		.05			

DDH: 76-04 UTM-N: 8676.0 UTM-E: 15107.6 UTM-ELEV: 4156.9 TOTAL DEPTH: 890.0 SECTION: 124
 RFE: S2 RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----		-----ASSAYS-----																			
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
628.7	632.0	73230	3.3	.0	2F64	3.89	.34	6.91	6.76	98.00		.14	5	25	30	.16		.16			
632.0	637.0	73231	5.0	.0	2F64	4.41	.17	5.67	5.50	70.29		.14	5	25	30	15.51		.16			
637.0	642.0	73232	5.0	.0	2E4	4.25	.02	3.08	4.95	36.00		.07	5	25	30	9.69		.16			
642.0	647.0	73233	5.0	.0	2E0	4.38	.11	1.28	2.52	2.70		.07	5	25	30	.02		.16			
647.0	652.0	73234	5.0	.0	2E0	3.79	.10	.67	.67	15.09			1	27	29	.02					
652.0	657.0	73235	5.0	.0	2E0	3.99	.04	.08	.26	3.39			1	27	29	.02					
657.0	662.0	73236	5.0	.0	2EC	3.68	.02	.11	.20				1	27	29	.02					
662.0	667.0	73237	5.0	.0	2EC	3.72	.02	.20	.17	11.59			1	27	29	.01					
667.0	672.0	73238	5.0	.0	2EC	3.89	.02	.24	.20				2	28	30	.02		.02			
672.0	677.0	73239	5.0	.0	2EC	3.72	.04	.17	.08				2	28	30	.01		.02			
677.0	682.0	73240	5.0	.0	2EC	3.45	.04	.28	.11	13.00			2	28	30	.02		.02			
682.0	687.0	73241	5.0	.0	2E0	4.51	.05	2.08	2.99	15.09		.01	2	28	30	.02		.02			
687.0	692.0	73242	5.0	.0	2E0	3.85	.05	1.27	.23	45.89		1.99	3	31	35	.01		.02			
692.0	697.0	73243	5.0	.0	2E4	5.34	.07	3.89	1.30	15.40		.07	3	31	35	.01		.02			
697.0	702.0	73244	5.0	.0	2E4	4.48	.24	2.81	2.73	14.40		.01	3	31	35	.02		.02			
702.0	707.0	73245	5.0	.0	2E0	4.33	.10	.80	1.35	7.49			3	31	35	.02		.02			
707.0	712.0	73246	5.0	.0	2E0	4.71	.07	.13	.11	7.90			3	32	35	.10		.02			
712.0	717.0	73247	5.0	.0	2G0	4.74	.07	4.37	8.75	39.79		.14	3	32	35	25.50		.02			
717.0	722.0	73248	5.0	.0	2H0	4.37	.44	2.37	3.62	21.89		.14	3	32	35	1.32		.02			
722.0	727.0	73249	5.0	.0	2EC	4.15	.04	.28	.26	8.90			3	32	35	.11		.02			
727.0	732.0	73250	5.0	.0	2EC	4.06	.05	1.50	2.10	4.09		.07	4	27	31	.02		.08			
732.0	737.0	73251	5.0	.0	2EC4	4.02	.14	3.39	4.02	28.80		.07	4	27	31	.08		.08			
737.0	742.0	73252	5.0	.0	2EC	3.70	.23	.69	1.33			.07	4	27	31	.13		.08			
742.0	747.0	73253	5.0	.0	2EC	3.83	.53	.19	.68	4.79			4	27	31	.02		.08			
747.0	752.0	73254	5.0	.0	1D4	3.31	.27	2.06	2.12	16.39		.21	6	14	21	.02		.17			
752.0	757.0	73255	5.0	.0	2EC	3.74	.23	1.03	1.44	8.19		.14	6	25	31	.02		.17			
757.0	762.0	73256	5.0	.0	2EC	4.08	.26	.57	1.76	6.50			6	25	31	.05		.17			
762.0	767.0	73257	5.0	.0	2E8	4.51	.45	.57	1.11	6.50			6	25	31	.02		.17			
767.0	772.0	73258	5.0	.0	2EF	4.15	.44	2.41	2.72	12.30		.07	4	27	32	.10		.08			
772.0	777.0	73259	5.0	.0	2F4	4.50	.08	4.95	10.19	18.80		.07	4	27	32	.02		.08			
777.0	782.0	73260	5.0	.0	2E1	4.09	.19	1.88	2.27	6.20		.07	4	27	32	.05		.08			
782.0	787.0	73261	5.0	.0	2E14	3.97	.05	2.75	5.41	18.80		.14	4	27	32	.05		.08			
787.0	792.0	73262	5.0	.0	2D0	3.29	.08	2.73	6.95	35.70		1.37	4	12	17	.05		.05			
792.0	797.0	73263	5.0	.0	2C0	3.37	.05	.49	1.69	19.89		.62	4	12	17	.05		.05			
797.0	802.0	73264	5.0	.0	2D4	3.62	.04	6.20	13.19	44.60		.21	4	12	17	.07		.05			
802.0	807.0	73265	5.0	.0	2D4	3.74	.08	6.90	16.39	56.89		.27	4	12	17	.11		.05			
807.0	812.0	73266	5.0	.0	2C0	2.89	.07	1.36	1.66	32.90		.55	4	3	8	.20		.08			
812.0	817.0	73267	5.0	.0	2D0	3.22	.17	3.00	4.70	53.79		1.92	4	3	8	.28		.08			

DDH: 76-05 UTM-N: 8584.0 UTM-E: 14797.0 UTM-ELEV: 4100.2 TOTAL DEPTH: 744.0 SECTION: 123+015
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

-----DEPTHS-----						-----ASSAYS-----																
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.	
486.0	488.0	73272	2.0	.0	1E19	2.91	.05	.06	.07	3.40				5	4	10	.40				.06	
488.0	490.0	73273	2.0	.0	2C9	3.08	.52	.17	.07	112.40				5	4	10	.11				.06	
490.0	492.4	73274	2.4	.0	2L14	2.90	.18	.30	.15	7.50				4	4	9	.69				.07	
492.4	493.9	73275	1.5	.0	1E19	2.77	.09	.06	.08	4.10				4	4	9	.45				.07	
493.9	495.0	73276	1.1	.0	2B9	2.96	.35	.17	.12					4	4	9	5.08				.07	
495.0	500.0	73277	5.0	.0	2B9(	3.02	.29	2.52	1.68	49.70				4	4	9	.97				.07	
500.0	505.0	73278	5.0	.0	2B0(	2.99	.12	.13	.05					4	4	9	2.36				.07	
505.0	510.0	73279	5.0	.0	2B0	2.79	.10	.11	.14					4	4	9	1.63				.07	
510.0	515.0	73280	5.0	.0	2C9(	3.27	.21	.22	.80	7.20				8	16	24	.35				.14	
515.0	517.5	73281	2.5	.0	2C9	3.08	.26	.45	.23	2.40				8	16	24	1.50				.14	
517.5	520.0	73282	2.5	.0	2D4	3.86	.03	8.32	16.80	108.00				8	16	24	.45				.14	
520.0	524.0	73283	4.0	.0	2G4	4.57	.05	4.47	6.90	46.30				8	16	24	25.76				.14	
524.0	525.0	73284	1.0	.0	2E43	4.11	.34	4.18	8.75	59.00				8	16	24	.03				.14	
525.0	530.0	73285	5.0	.0	2E43	4.13	.27	5.44	8.22	59.70				8	16	24	.06				.14	
530.0	535.0	73286	5.0	.0	2H49	3.80	.30	4.83	5.35	61.00				19	12	32	9.99				.08	
535.0	539.7	73287	4.7	.0	2H49	4.22	.35	6.34	3.84	61.50				19	12	32	.07				.08	
539.7	544.4	73288	4.7	.0	2C39	3.48	.29	.66	1.91	20.60				19	12	32	.79				.08	
544.4	546.4	73289	2.0	.0	2G4	4.08	.06	5.18	5.66	78.90				19	12	32	16.86				.08	
563.0	564.0	73291	1.0	.0	1D41	2.83	.03	.10	.16	6.90				2	2	5	2.44				.05	
564.0	565.3	73292	1.3	.0	1E19	2.86	.04	.18	.40	6.00				1	1	3	2.67				.05	
565.3	570.0	73293	4.7	.0	1D4(	2.90	.05	.27	.64	5.50				2	2	5	3.17				.05	
570.0	572.2	73294	2.2	.0	1E19	2.92	.03	.89	1.06	27.80				11	10	22	2.19				.15	
572.2	575.0	73295	2.8	.0	1D4(	2.99	.06	1.69	1.88	32.60				11	10	22	4.61				.15	
575.0	577.2	73296	2.2	.0	1D4	2.91	.04	.54	.90					11	10	22	2.37				.15	
577.2	580.0	73297	2.8	.0	2K49	4.15	.33	5.37	7.55	56.90				11	10	22	.08				.15	
580.0	585.0	73298	5.0	.0	2K79	4.09	.25	3.17	3.07	68.60				11	10	22	1.50				.15	
585.0	588.0	73299	3.0	.0	2H9&	3.61	.36	2.18	2.10	46.60				11	10	22	.78				.15	
588.0	590.0	73300	2.0	.0	1H4*	2.88	.08	.16	.27					11	10	22	.19				.15	
590.0	595.7	73301	5.7	.0	1H4*	2.92	.08	2.78	1.58	46.60				14	9	24	.45				.14	
595.7	600.0	73302	4.3	.0	2H39	4.55	.38	3.33	2.76	31.20				14	9	24	.06				.14	
600.0	605.0	73303	5.0	.0	2Q9(	3.28	.27	3.07	1.01	60.30				14	9	24	.12				.14	
605.0	610.0	73304	5.0	.0	2C9(	3.11	.33	.67	.26	30.20				14	9	24	.09				.14	
610.0	612.0	73305	2.0	.0	2C9(	3.58	.23	.89	.55	28.80				7	29	36	.04				.22	
612.0	614.4	73306	2.4	.0	1H4*	3.01	.10	4.65	.46	30.90				7	29	36	.16				.22	
614.4	615.9	73307	1.5	.0	2E39	3.88	.29	1.59	.35	42.50				7	29	36	.05				.22	
615.9	620.0	73308	4.1	.0	2E9&	4.89	.24	1.33	.84	17.10				7	29	36	.07				.22	
620.0	625.0	73309	5.0	.0	2E9&	4.99	.27	2.27	1.49	18.50				7	29	36	.05				.22	
625.0	626.0	73310	1.0	.0	2E9&	4.83	.31	1.60	.92	11.60				7	29	36	.05				.22	
626.0	630.5	73311	4.5	.0	2F49	4.64	.26	8.90	9.43	99.40				7	29	36	.05				.22	
630.5	635.0	73312	4.5	.0	2E49	4.80	.20	4.99	3.61	55.50				4	33	38	.05				.09	
635.0	637.0	73313	2.0	.0	2E4(	4.70	.19	5.05	2.24	24.00				4	33	38	.04				.09	
637.0	640.0	73314	3.0	.0	2E9	4.90	.39	1.89	1.04	20.60				4	33	38	.09				.09	
640.0	642.0	73315	2.0	.0	2E9	4.70	.37	1.24	2.06	16.40				4	33	38	.31				.09	
642.0	646.0	73316	4.0	.0	2E9&	3.91	.24	.49	.61	13.00				4	33	38	.04				.09	
646.0	650.0	73317	4.0	.0	2F4(	4.96	.08	5.09	6.64	42.50				4	33	38	.05				.09	
650.0	655.0	73318	5.0	.0	2F49	4.81	.21	4.85	8.58	39.80				5	35	40	.03				.17	
655.0	660.0	73319	5.0	.0	2E0(	4.92	.07	1.88	5.76	3.40				5	35	40	.04				.17	
660.0	665.0	73320	5.0	.0	2E0(	4.48	.37	2.83	3.98	32.60				5	35	40	.04				.17	
665.0	670.0	73321	5.0	.0	2F49	4.76	.26	2.47	3.23	26.70				5	35	40	.06				.17	
670.0	675.0	73322	5.0	.0	2E49	4.56	.27	1.64	2.36	15.10				6	26	32	.13				.12	

DDH: 76-05 UTM-N: 8584.0 UTM-E: 14797.0 UTM-ELEV: 4100.2 TOTAL DEPTH: 744.0 SECTION: 123+015
RFE: 52 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	ASSAYS														
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
675.0	678.2	73323	3.2	.0	2E48	4.72	.26	2.88	3.70	12.30			6	26	32	.04		.12			
678.2	680.0	73324	1.8	.0	2C0	3.07	.13	.30	.53				6	26	32	.19		.12			
680.0	683.0	73325	3.0	.0	2C9	3.53	.25	2.54	1.50	8.20			6	26	32	.13		.12			
683.0	685.0	73326	2.0	.0	2E10	4.78	.13	3.64	6.66	25.40			6	26	32	.05		.12			
685.0	688.0	73327	3.0	.0	2E10	4.45	.15	3.45	5.84	20.60			6	26	32	.04		.12			
688.0	690.0	73328	2.0	.0	2F4	4.80	.06	6.86	12.50	13.00			6	26	32	.05		.12			
690.0	695.0	73329	5.0	.0	2F4	4.79	.05	4.63	8.83	29.50			6	26	32	.03		.12			
695.0	699.5	73330	4.5	.0	2E41	4.29	.16	2.37	5.28	19.20			5	25	31	.07		.04			
699.5	700.5	73331	1.0	.0	2D5	3.30	.14	3.00	5.37	52.80			5	25	31	.21		.04			
700.5	705.0	73332	4.5	.0	2E41	4.65	.15	4.25	5.81	3.40			5	25	31	.04		.04			
705.0	709.0	73333	4.0	.0	2D0&	3.26	.11	1.62	3.32	19.50			5	25	31	.21		.04			
709.0	710.0	73334	1.0	.0	2E13	4.76	.06	.10	.61	13.70			5	25	31	.03		.04			
710.0	712.5	73335	2.5	.0	2E13	4.01	.14	.44	1.00	13.70			5	25	31	.07		.04			
712.5	715.0	73336	2.5	.0	2D9	3.03	.24	1.98	3.83	13.00			6	5	11	.15		.07			
715.0	720.0	73337	5.0	.0	2C00	3.47	.12	1.65	2.27	19.20			6	5	11	.17		.07			
720.0	725.3	73338	5.3	.0	2B0	2.99	.15	.28	.23	47.30			6	5	11	.15		.07			

DDH: 76-06 UTM-N: 8805.2 UTM-E: 14600.1 UTM-ELEV: 4058.7 TOTAL DEPTH: 801.0 SECTION: 121+000
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Pt %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
489.4	492.3	73344	2.9	.0	2C9	3.04	.24	.20	.24	5.80			2	11	13	.37		.09			
492.3	493.4	73345	1.1	.0	2A13	3.15	.28	.23	.30	12.00			2	11	13	.08		.09			
493.4	498.4	73346	5.0	.0	2C9	3.27	.41	.34	.32	27.40			2	11	13	.11		.09			
498.4	500.9	73347	2.5	.0	2C9	3.13	.33	.42	.61	17.50			2	11	13	.07		.09			
500.9	502.0	73348	1.1	.0	2A41	3.37	.12	2.40	6.75	30.50			2	11	13	.44		.09			
502.0	506.0	73349	4.0	.0	2D49	3.52	.23	6.45	11.20	63.10			2	11	13	.19		.09			
506.0	507.0	73350	1.0	.0	2F48	4.68	.10	9.82	8.35	139.60			2	11	13	2.44		.09			
507.0	512.0	73351	5.0	.0	2G4	4.58	.17	8.41	6.45	102.50			2	15	17	26.39		.38			
512.0	517.0	73352	5.0	.0	2G4	4.65	.15	7.13	6.62	95.00			2	15	17	26.12		.38			
517.0	522.0	73353	5.0	.0	2G4	4.61	.16	6.22	6.15	82.60			2	15	17	28.10		.38			
522.0	527.0	73354	5.0	.0	2G4	4.63	.09	6.39	6.54	86.10			2	15	17	29.39		.38			
527.0	532.0	73355	5.0	.0	2G4	4.85	.11	8.00	6.70	114.50			9	10	20	28.69		.32			
532.0	537.0	73356	5.0	.0	2G4	4.69	.11	7.38	7.22	102.50			9	10	20	32.27		.32			
537.0	541.6	73357	4.6	.0	2G4	4.65	.10	6.93	7.08	94.30			9	10	20	27.83		.32			
541.6	544.5	73358	2.9	.0	2H41	3.89	.15	4.59	5.62	64.50			9	10	20	4.89		.32			
544.5	545.8	73359	1.3	.0	2G91	3.50	.63	1.86	.54	38.70			9	10	20	15.21		.32			
545.8	546.7	73360	.9	.0	2H16	3.62	.16	3.19	1.53	47.00			9	10	20	9.81		.32			
546.7	549.4	73361	2.7	.0	2G1	3.19	.15	.75	.80	14.70			9	10	20	18.14		.32			
549.4	554.4	73362	5.0	.0	2G1	3.15	.07	.72	1.10	10.60			9	10	20	29.46		.32			
554.4	559.4	73363	5.0	.0	2C6	2.99	.05	1.66	2.22	30.50			9	10	20	7.49		.32			
559.4	564.4	73364	5.0	.0	2C6	2.99	.03	1.27	1.29	21.90			9	10	20	6.08		.32			
564.4	566.3	73365	1.9	.0	2D08	3.12	.06	2.42	5.93	39.10			9	10	20	.88		.32			
566.3	571.3	73366	5.0	.0	2A41	3.00	.07	1.95	2.22	28.50			9	10	20	.81		.32			
571.3	576.3	73367	5.0	.0	2D5	2.92	.10	2.51	6.37	33.30			12	14	27	.15		.11			
576.3	578.4	73368	2.1	.0	2H43	4.41	.24	7.61	12.30	87.80			12	14	27	.09		.11			
578.4	579.5	73369	1.1	.0	2F49	4.39	.23	5.15	7.98	68.20			12	14	27	.07		.11			
579.5	580.4	73370	.9	.0	2H49	4.18	.20	4.61	5.56	48.30			12	14	27	.13		.11			
580.4	581.0	73371	.6	.0	2E49	4.55	.38	5.20	4.80	78.50			12	14	27	.06		.11			
581.0	581.5	73372	.5	.0	2H43	4.18	.20	4.61	5.56	48.30			12	14	27	.13		.11			
581.5	584.5	73373	3.0	.0	2F46	4.50	.21	6.28	9.25	78.20			12	14	27	8.52		.11			
584.5	585.0	73374	.5	.0	2F49	4.59	.46	6.52	9.75	85.40			12	14	27	.23		.11			
585.0	586.0	73375	1.0	.0	2E49	4.27	.40	3.38	3.60	44.90			12	14	27	.55		.11			
586.0	588.0	73376	2.0	.0	2H69	4.37	.29	3.60	1.56	58.30			12	14	27	14.32		.11			
588.0	593.0	73377	5.0	.0	2G9	4.59	2.30	1.88	.70	72.70			17	15	32	9.09		.11			
593.0	597.0	73378	4.0	.0	2G49	4.72	.20	2.55	1.56	32.60			3	32	36	13.14		.08			
597.0	599.7	73379	2.7	.0	2G4	4.98	.10	5.15	5.85	47.30			3	32	36	33.36		.08			
599.7	600.2	73380	.5	.0	2E5	4.85	.16	1.70	.90	15.80			3	32	36	1.20		.08			
600.2	603.0	73381	2.8	.0	2E49	4.72	.22	1.66	3.13	21.90			3	32	36	.14		.08			
603.0	604.0	73382	1.0	.0	2E4	4.48	.09	3.39	5.48	36.30			3	32	36	.77		.08			
604.0	604.5	73383	.5	.0	2E46	4.76	.11	2.44	1.80	27.80			3	32	36	8.41		.08			
604.5	609.7	73384	5.2	.0	2E0	4.81	.11	1.00	.46	14.70			3	32	36	2.82		.08			
609.7	612.5	73385	2.8	.0	2G4	4.78	.05	4.29	6.65	38.10			4	26	31	24.74		.13			
612.5	614.5	73386	2.0	.0	2E46	4.83	.06	2.69	4.52	25.70			4	26	31	1.12		.13			
614.5	619.0	73387	4.5	.0	2E46	4.74	.16	4.28	5.10	49.00			4	26	31	6.48		.13			
619.0	620.0	73388	1.0	.0	2E4	4.72	.09	3.38	6.48	40.10			4	26	31	.09		.13			
620.0	623.0	73389	3.0	.0	2E1	3.70	.11	.82	.56	29.80			4	26	31	.69		.13			
623.0	624.8	73390	1.8	.0	2G4	4.90	.07	5.34	8.26	48.70			4	26	31	35.00		.13			
624.8	625.1	73391	.3	.0	2E1	3.41	.07	.11	.27	9.20			4	26	31	.06		.13			
625.1	625.6	73392	.5	.0	2E1	4.20	.16	.59	.61	17.80			4	26	31	.06		.13			
625.6	626.1	73393	.5	.0	2E43	4.69	.22	5.02	6.28	35.70			4	26	31	.05		.13			
626.1	628.0	73394	1.9	.0	2E43	4.50	.25	2.88	3.60	23.30			4	26	31	.67		.13			

DDH: 76-06 UTM-N: 8805.2 UTM-E: 14600.1 UTM-ELEV: 4058.7 TOTAL DEPTH: 801.0 SECTION: 121+000
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

-----DEPTHS-----						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
628.0	630.1	73395	2.1	.0	2E43	4.65	.38	2.65	4.82	26.40			5	22	28	.04		.16			
630.1	633.4	73396	3.3	.0	2F47	4.24	.81	3.62	8.20	34.30			5	22	28	.13		.16			
633.4	638.4	73397	5.0	.0	2D9	3.03	.34	.85	4.46	17.50			5	22	28	.41		.16			
638.4	640.3	73398	1.9	.0	2D0	3.13	.13	.67	3.38	18.80			5	22	28	.22		.16			
640.3	641.0	73399	.7	.0	2E4	4.74	.11	2.12	5.46	20.90			5	22	28	.04		.16			
641.0	643.3	73400	2.3	.0	2E49	4.31	.21	2.08	3.90	16.50			5	22	28	.03		.16			
643.3	645.2	73401	1.9	.0	2E49	4.27	.25	2.30	4.18	13.00			5	22	28	.03		.16			
645.2	650.7	73402	5.5	.0	2E89	4.24	.52	1.44	2.51	14.70			5	22	28	.05		.16			
650.7	656.0	73403	5.3	.0	2E89	4.50	.36	1.37	1.64	13.70			4	37	41	.14		.11			
656.0	660.0	73404	4.0	.0	2E19	4.02	.41	1.19	1.09	15.80			4	37	41	.03		.11			
660.0	660.8	73405	.8	.0	2E8	4.55	.15	.30	.40	9.90			4	37	41	.04		.11			
660.8	661.4	73406	.6	.0	2E0	4.61	.10	1.31	2.42	14.70			4	37	41	.05		.11			
661.4	662.2	73407	.8	.0	2E9	4.67	.21	.53	.81	14.70			4	37	41	.11		.11			
662.2	662.5	73408	.3	.0	2E4	4.50	.17	1.64	3.21	14.40			4	37	41	.03		.11			
662.5	667.5	73409	5.0	.0	2E89	4.42	.36	.30	.78	13.40			4	37	41	.04		.11			
667.5	671.3	73410	3.8	.0	2E9	4.55	.39	.30	1.30	14.40			6	28	34	.11		.11			
671.3	675.9	73411	4.6	.0	2F1	4.29	.21	2.00	4.40	17.50			6	28	34	.06		.11			
675.9	677.0	73412	1.1	.0	2F10	3.48	.36	5.00	3.44	40.80			6	28	34	.19		.11			
677.0	678.0	73413	1.0	.0	2E4&	4.67	.19	1.85	3.80	18.20			6	28	34	.05		.11			
678.0	680.5	73414	2.5	.0	2E4	4.44	.05	4.33	4.33	27.80			6	28	34	.07		.11			
680.5	681.0	73415	.5	.0	2E1	4.72	.04	.87	.87	13.70			6	28	34	.06		.11			
681.0	682.0	73416	1.0	.0	2E1	4.27	.06	1.21	1.21	14.40			6	28	34	.03		.11			
682.0	685.2	73417	3.2	.0	2E1	5.81	.08	1.75	1.75	20.20			6	28	34	.09		.11			
685.2	689.1	73418	3.9	.0	2H43	3.48	.41	4.00	7.83	29.10			6	28	34	.04		.11			
689.1	692.0	73419	2.9	.0	2D39	2.91	.81	.61	3.95	85.40			7	7	14	.18		.05			
692.0	696.0	73420	4.0	.0	2A4	3.11	.17	1.78	4.60	30.20			7	7	14	.15		.05			
696.0	700.0	73421	4.0	.0	2A40	3.04	.34	3.40	3.72	54.20			7	7	14	.19		.05			
700.0	704.5	73422	4.5	.0	2A0	2.96	.17	1.30	2.42	27.80			7	7	14	.25		.05			
704.5	705.7	73423	1.2	.0	2A0	2.88	.05	1.72	2.03	38.10			7	7	14	.17		.05			
705.7	707.7	73424	2.0	.0	2A0	2.75	.05	.79	2.70	17.10			7	7	14	.18		.05			
707.7	712.7	73425	5.0	.0	2A4	2.75	.04	1.12	3.92	30.50			3	7	10	.15		.03			
712.7	717.7	73426	5.0	.0	2A4	2.62	.09	.90	3.20	34.30			3	7	10	.16		.03			
717.7	719.7	73427	2.0	.0	2A0	2.76	.14	.18	.15	14.70			3	7	10	.18		.03			
719.7	723.2	73428	3.5	.0	2A0	2.54	.11	.13	.18	15.80			3	7	10	.19		.03			
723.2	723.7	73429	.5	.0	2A0	3.44	.23	.14	.30	20.20			3	7	10	.09		.03			
723.7	727.0	73430	3.3	.0	2A0	2.42	.05	.95	1.61	63.80			3	7	10	.28		.03			
727.0	727.9	73431	.9	.0	0Q9	2.72	.30	1.02	.37	93.60			5	8	14	.05		.02			
727.9	730.0	73432	2.1	.0	2B40	2.92	.13	4.35	3.60	154.30			5	8	14	.04		.02			
730.0	731.8	73433	1.8	.0	2D5L	2.92	.13	4.35	3.60	154.30			5	8	14	.05		.02			
731.8	736.8	73434	5.0	.0	2D5L	2.86	.15	1.68	5.55	44.60			5	8	14	.20		.02			
736.8	741.8	73435	5.0	.0	2D5L	2.88	.15	2.24	2.90	175.20			5	8	14	.15		.02			
741.8	746.8	73436	5.0	.0	2D5L	3.03	.12	2.81	4.74	50.10			5	8	14	.23		.02			
746.8	750.5	73437	3.7	.0	2D79	3.22	.42	1.64	4.43	26.40			5	8	14	.14		.02			
750.5	755.0	73438	4.5	.0	2D79	3.07	.27	2.00	6.45	32.90			8	3	11	.13		.04			
755.0	756.3	73439	1.3	.0	2D5	2.99	.13	4.80	8.91	48.00			8	3	11	.16		.04			
756.3	761.3	73440	5.0	.0	2A41	2.72	.06	3.30	4.50	55.20			8	3	11	.22		.04			
761.3	766.3	73441	5.0	.0	2A4	3.22	.12	1.60	4.45	35.70			8	3	11	.15		.04			
766.3	771.3	73442	5.0	.0	2A0	2.46	.11	.33	1.90	8.20			8	3	11	.16		.04			

DDH: 76-07 UTM-N: 8614.0 UTM-E: 14406.4 UTM-ELEV: 4051.3 TOTAL DEPTH: 787.0 SECTION: 121+000
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

-----DEPTHS-----		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %
516.3	518.5	73448	2.2	.0	2D4	3.13	.12	5.85	10.40	45.60			4	12	17	.14		.09		
518.5	520.5	73449	2.0	.0	2C0	3.06	.17	.65	2.95	12.70			4	12	17	.14		.09		
520.5	521.6	73450	1.1	.0	2E4	4.50	.06	2.89	6.00	35.30			4	12	17	.17		.09		
521.6	525.0	73451	3.4	.0	2G4	4.59	.13	6.60	6.55	86.70			8	21	29	12.46		.29		
525.0	530.0	73452	5.0	.0	2E46	4.61	.24	7.16	6.10	102.20			8	21	29	5.80		.29		
530.0	535.0	73453	5.0	.0	2E46	4.63	.19	6.48	6.36	109.70			8	21	29	3.93		.29		
535.0	539.0	73454	4.0	.0	2E43	4.10	.23	6.24	7.02	91.90			8	21	29	1.48		.29		
539.0	540.3	73455	1.3	.0	1D4	2.79	.20	1.06	.39	30.50			8	21	29	1.41		.29		
540.3	542.0	73456	1.7	.0	2J4	3.60	.10	5.85	20.60	88.80			8	21	29	.53		.29		
542.0	545.0	73457	3.0	.0	2J4	3.60	.10	5.85	20.60	88.80			8	21	29	.53		.29		
545.0	549.2	73458	4.2	.0	2H43	4.27	.43	5.70	7.37	77.10			23	12	35	.13		.20		
549.2	550.2	73459	1.0	.0	2H43	4.00	.30	5.16	5.23	60.70			23	12	35	.17		.20		
550.2	553.9	73460	3.7	.0	2H39	4.02	.29	4.37	5.00	51.40			23	12	35	.15		.20		
553.9	555.0	73461	1.1	.0	2H39	3.75	.26	2.43	5.00	29.50			23	12	35	.15		.20		
555.0	559.9	73462	4.9	.0	2H39	4.20	.33	3.77	5.70	47.70			23	12	35	.15		.20		
559.9	560.7	73463	.8	.0	2H39	4.10	.33	3.86	5.91	44.90			23	12	35	.16		.20		
560.7	562.5	73464	1.8	.0	2E43	3.24	.13	3.41	6.23	39.80			23	12	35	.18		.20		
562.5	565.0	73465	2.5	.0	2D0	2.87	.06	.83	3.39	15.80			9	28	37	.13		.10		
565.0	565.8	73466	.8	.0	2D4	3.62	.16	4.75	20.60	75.10			9	28	37	.17		.10		
565.8	566.6	73467	.8	.0	2D43	4.20	.43	4.70	7.68	41.50			9	28	37	.15		.10		
566.6	568.1	73468	1.5	.0	2H43	4.17	.34	6.81	12.00	87.80			9	28	37	.17		.10		
568.1	571.0	73469	2.9	.0	2E49	4.37	.76	3.30	4.33	36.70			9	28	37	.13		.10		
571.0	573.5	73470	2.5	.0	2H39	4.12	.69	1.79	.84	27.40			9	28	37	.14		.10		
573.5	575.5	73471	2.0	.0	2E8	4.29	.17	1.96	.94	23.00			9	28	37	.15		.10		
575.5	580.5	73472	5.0	.0	2E9	4.46	.30	.37	.47	6.50			9	28	37	.15		.10		
580.5	583.6	73473	3.1	.0	2E9	4.69	.62	.30	1.01	12.70			9	28	37	.13		.10		
583.6	585.0	73474	1.4	.0	2F4	4.57	.12	6.85	9.15	52.50			4	26	30	.15		.06		
585.0	590.0	73475	5.0	.0	2F4	4.55	.14	7.19	8.50	53.10			4	26	30	.16		.06		
590.0	592.0	73476	2.0	.0	2E49	4.65	.24	3.24	1.98	28.10			4	26	30	.10		.06		
592.0	596.0	73477	4.0	.0	2E9	4.74	.39	.92	.98	15.80			4	26	30	.14		.06		
596.0	596.5	73478	.5	.0	2D9	4.46	.27	4.76	5.00	49.40			4	26	30	.19		.06		
596.5	597.0	73479	.5	.0	0Q9	3.82	.63	3.56	5.41	78.20			4	26	30	.20		.06		
597.0	602.0	73480	5.0	.0	2B0	2.85	.08	1.00	2.10	20.90			4	26	30	.13		.06		
602.0	607.0	73481	5.0	.0	2B0	2.81	.13	.68	1.31	16.80			3	22	26	.18		.05		
607.0	612.0	73482	5.0	.0	2B49	3.01	.30	1.35	4.90	37.70			3	22	26	.21		.05		
612.0	615.5	73483	3.5	.0	2E4	4.67	.02	5.20	4.90	48.00			3	22	26	.14		.05		
615.5	620.5	73484	5.0	.0	2E4	4.44	.03	4.02	5.70	39.40			3	22	26	.16		.05		
620.5	625.5	73485	5.0	.0	2E49	4.83	.57	4.72	5.72	52.10			3	22	26	.17		.05		
625.5	630.5	73486	5.0	.0	2E4	4.63	.12	3.77	6.80	35.30			7	28	35	.15		.05		
630.5	631.4	73487	.9	.0	2E4	4.22	.07	4.08	6.98	49.40			7	28	35	.16		.05		
631.4	636.4	73488	5.0	.0	2E49	4.72	.22	3.91	6.89	43.90			7	28	35	.15		.05		
636.4	640.0	73489	3.6	.0	2H43	3.97	.52	4.51	7.06	41.80			7	28	35	.14		.05		
640.0	641.0	73490	1.0	.0	2E4	4.02	.17	1.03	4.54	13.40			7	28	35	.16		.05		
641.0	643.0	73491	2.0	.0	1D4	3.11	.23	.85	1.55	52.10			7	28	35	.15		.05		
643.0	646.0	73492	3.0	.0	2B49	3.02	.20	2.20	3.80	41.10			5	4	9	.24		.04		
646.0	651.0	73493	5.0	.0	2B4	3.17	.16	4.47	3.85	91.20			5	4	9	.14		.04		
651.0	656.0	73494	5.0	.0	2B4	3.01	.09	4.18	3.23	95.30			5	4	9	.31		.04		
656.0	661.0	73495	5.0	.0	2B0	2.79	.07	.49	1.57	19.90			5	4	9	.28		.04		
661.0	666.0	73496	5.0	.0	2B4	3.16	.06	5.93	1.79	128.20			6	6	12	.23		.04		
666.0	669.3	73497	3.3	.0	2A0	2.79	.06	1.16	2.22	23.70			3	1	5	.21		.06		
669.3	670.0	73498	.7	.0	1D4	2.79	.08	.50	.29	12.70			3	1	5	.17		.06		

DDH: 76-07 UTM-N: 8614.0 UTM-E: 14406.4 UTM-ELEV: 4051.3 TOTAL DEPTH: 787.0 SECTION: 121+000
RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

-----DEPTHS-----				-----ASSAYS-----																
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
670.0	675.0	73499	5.0	.0	1D4	2.79	.03	.05	.08				3	1	5	.25		.06		
675.0	680.0	73500	5.0	.0	1D4	2.72	.02	.07	.14				3	1	5	.18		.06		
680.0	685.0	73501	5.0	.0	1D4	2.72	.01	.09	.12	8.90			3	1	5	.18		.06		
685.0	685.6	73502	.6	.0	2A4	2.77	.03	1.83	3.40	31.90			3	1	5	.15		.06		
685.6	686.2	73503	.6	.0	1D4	2.67	.04	.09	.59	3.10			3	1	5	.30		.06		
686.2	688.2	73504	2.0	.0	2A4	2.83	.04	1.64	2.82	22.30			3	1	5	.20		.06		
688.2	690.5	73505	2.3	.0	1D4	2.76	.10	.45	.36	22.30			3	1	5	.88		.06		
690.5	691.9	73506	1.4	.0	2A0	2.87	.08	.97	2.77	31.90			3	1	5	.15		.06		

DDH: 76-10 UTM-N: 8397.2 UTM-E: 14213.9 UTM-ELEV: 4009.1 TOTAL DEPTH: 626.0 SECTION: 121+000
RFE: 92 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

---DEPTHS---						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
521.5	524.2	73626	2.7	.0	2C06	3.34	.14	.40	.95	2.10			7	18	26	.06		.05			
524.2	529.2	73627	5.0	.0	2D01	3.04	.11	1.50	3.40	18.50			7	18	26	.18		.05			
529.2	530.5	73628	1.3	.0	2H43	4.57	.27	6.63	9.25	94.60			7	18	26	.37		.05			
530.5	531.3	73629	.8	.0	2H43	4.29	.36	3.80	5.88	23.30			7	18	26	.05		.05			
531.3	534.0	73630	2.7	.0	2H43	4.59	.21	8.50	12.40	36.00			7	18	26	.06		.05			
534.0	537.0	73631	3.0	.0	2H43	4.50	.06	5.34	8.25	34.30			7	18	26	.07		.05			
537.0	538.0	73632	1.0	.0	2D4	4.46	.10	4.54	7.65	42.50			3	4	7	.11		.04			
538.0	542.0	73633	4.0	.0	2C0	2.97	.18	.80	2.50	18.50			3	4	7	.27		.04			
542.0	545.0	73634	3.0	.0	2C0	2.84	.14	1.08	1.37	53.40			3	4	7	.24		.04			
545.0	550.0	73635	5.0	.0	2A0	2.91	.08	.91	1.89	24.70			3	4	7	.22		.04			
550.0	555.0	73636	5.0	.0	2A4	2.91	.04	1.97	4.42	21.20			3	4	7	.36		.04			
555.0	560.0	73637	5.0	.0	2A0	2.92	.06	.85	.95	10.30			3	4	7	.37		.04			

DDH: 76-11 UTM-N: 8618.1 UTM-E: 13987.0 UTM-ELEV: 3992.0 TOTAL DEPTH: 595.0 SECTION: 119+000
RFE: 92 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

-----DEPTHS-----							-----ASSAYS-----													
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
501.0	506.0	73643	5.0	.0	2B45	3.09	.05	3.48	5.48	38.70		4	8	13	.37		.07			
506.0	511.0	73644	5.0	.0	009	2.92	.03	2.28	5.33	30.50		4	8	13	.23		.07			
511.0	516.0	73645	5.0	.0	2B45	2.96	.05	1.80	3.85	26.40		4	8	13	.32		.07			
516.0	521.0	73646	5.0	.0	2E42	4.62	.12	4.90	7.90	56.90		4	8	13	.11		.07			
521.0	526.0	73647	5.0	.0	2E42	3.73	.17	4.60	6.58	65.80		7	8	15	.06		.18			
526.0	531.0	73648	5.0	.0	009	2.90	.03	5.33	2.20	90.90		7	8	15	.16		.18			
531.0	536.0	73649	5.0	.0	2J41	3.76	.25	11.90	13.50	310.00		7	8	15	.29		.18			
536.0	541.0	73650	5.0	.0	2J41	4.00	.27	12.30	16.60	384.00		7	8	15	.17		.18			
541.0	544.0	73651	3.0	.0	2J4	3.26	.11	6.85	8.88	132.40		7	8	15	.24		.18			

DDH: 76-13 UTM-N: 9003.1 UTM-E: 14399.2 UTM-ELEV: 4002.2 TOTAL DEPTH: 714.0 SECTION: 119+000
 RFE: 82 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	ASSAYS													
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Pt %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %
481.5	486.5	73735	5.0	.0	2E01	3.25	.17	.18	1.29	17.20			3	13	17	.05		.03		
486.5	490.3	73736	3.8	.0	2C0	3.04	.20	.62	3.05	32.20			3	13	17	.07		.03		
490.3	494.2	73737	3.9	.0	2D05	3.28	.05	1.00	7.48	22.60			3	13	17	.08		.03		
494.2	499.2	73738	5.0	.0	2G42	4.65	.17	5.80	5.91	85.40			6	23	29	12.87		.30		
499.2	504.2	73739	5.0	.0	2G42	4.63	.12	4.97	5.82	73.00			6	23	29	13.74		.30		
504.2	509.2	73740	5.0	.0	2G42	4.55	.11	5.22	5.32	84.00			6	23	29	22.42		.30		
509.2	514.0	73741	4.8	.0	2G42	4.37	.34	4.40	4.90	80.20			6	23	29	7.30		.30		
514.0	519.0	73742	5.0	.0	2E44	4.42	.08	3.07	2.71	57.30			5	11	16	.33		.24		
519.0	524.0	73743	5.0	.0	2D07	3.38	.22	3.62	4.16	69.60			5	11	16	5.24		.24		
524.0	529.0	73744	5.0	.0	2A4	2.92	.04	2.27	4.53	47.70			5	11	16	.37		.24		
529.0	534.0	73745	5.0	.0	2A4	2.90	.04	1.30	3.98	36.30			5	11	16	.44		.24		
534.0	539.0	73746	5.0	.0	2A4	2.85	.04	1.79	3.78	43.60			5	5	11	.98		.13		
539.0	544.0	73747	5.0	.0	2A4	2.79	.03	1.21	2.92	35.30			5	5	11	.61		.13		
544.0	549.0	73748	5.0	.0	2A4	3.11	.10	1.94	5.54	47.30			5	5	11	.88		.13		
549.0	554.0	73749	5.0	.0	2G4	4.08	.28	7.63	5.87	147.40			5	5	11	10.53		.13		
554.0	559.0	73750	5.0	.0	2G42	4.57	.17	5.51	7.20	112.10			6	21	27	28.32		.10		
559.0	564.0	73751	5.0	.0	2F46	4.42	.12	5.49	8.80	90.50			6	21	27	5.55		.10		
564.0	569.0	73752	5.0	.0	2G4	4.57	.08	5.86	7.70	75.10			6	21	27	26.56		.10		
569.0	574.0	73753	5.0	.0	2F4	4.78	.05	6.78	11.70	63.80			6	21	27	.49		.10		
574.0	579.0	73754	5.0	.0	2F0	4.31	.23	3.00	3.90	31.20			5	34	40	.37		.17		
579.0	584.0	73755	5.0	.0	2E8	4.50	.18	1.60	2.57	20.20			5	34	40	.07		.17		
584.0	589.0	73756	5.0	.0	2E8	4.10	.26	1.78	2.46	17.10			5	34	40	.06		.17		
589.0	594.0	73757	5.0	.0	2E8	4.52	.19	1.81	4.00	14.40			5	34	40	.05		.17		
594.0	599.0	73758	5.0	.0	2E8	4.60	.59	1.73	2.86	23.00			4	35	39	.07		.08		
599.0	604.0	73759	5.0	.0	2F0	4.72	.22	5.08	4.30	24.00			4	35	39	.04		.08		
604.0	609.0	73760	5.0	.0	2F0	4.86	.31	2.68	4.53	21.60			4	35	39	.37		.08		
609.0	614.0	73761	5.0	.0	2F0	4.50	.15	3.88	5.89	30.20			4	35	39	.09		.08		
614.0	619.0	73762	5.0	.0	2F0	4.75	.13	3.85	5.52	29.80			5	27	32	.06		.03		
619.0	624.0	73763	5.0	.0	2F0	4.81	.08	3.95	5.39	23.70			5	27	32	.06		.03		
624.0	629.0	73764	5.0	.0	2F0	4.70	.11	3.46	6.25	28.80			5	27	32	.10		.03		
629.0	634.0	73765	5.0	.0	2A0	3.02	.08	.73	2.62	19.90			5	27	32	.18		.03		
634.0	639.0	73766	5.0	.0	2A0	2.81	.05	1.18	1.81	36.70			2	4	6	.19		.02		
639.0	644.0	73767	5.0	.0	2A0	2.85	.09	.88	2.29	25.70			2	4	6	.19		.02		
644.0	649.0	73768	5.0	.0	2A4	2.81	.07	1.30	3.26	26.10			2	4	6	.24		.02		
649.0	654.0	73769	5.0	.0	2A0	2.70	.04	.79	2.27	9.30			2	4	6	.20		.02		
654.0	659.0	73770	5.0	.0	2A4	2.82	.03	1.30	3.28	18.20			3	1	5	.17		.03		
659.0	660.5	73771	1.5	.0	2B4	3.00	.10	1.56	4.27	25.70			3	1	5	.09		.03		

DDH: 76-14 UTM-N: 9203.0 UTM-E: 14598.0 UTM-ELEV: 4002.6 TOTAL DEPTH: 611.0 SECTION: 119+000
RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

---DEPTHS---		-----ASSAYS-----																		
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
444.0	449.0	73777	5.0	.0	2G48	4.09	.19	4.11	6.52	76.10		16	16	32	5.10		.22			
449.0	454.0	73778	5.0	.0	2H4	4.20	.17	5.00	7.90	85.70		16	16	32	6.17		.22			
454.0	459.0	73779	5.0	.0	2G4	3.67	.15	2.73	3.24	48.00		9	10	19	5.45		.22			
459.0	464.0	73780	5.0	.0	2L2	3.06	.12	1.08	1.02	15.10		9	10	19	4.71		.22			
464.0	469.0	73781	5.0	.0	2E46	3.90	.17	7.58	8.78	103.90		9	10	19	2.93		.22			
469.0	474.0	73782	5.0	.0	1D4	3.09	.52	1.68	1.95	49.40		9	10	19	2.54		.22			
474.0	479.0	73783	5.0	.0	1D4	2.96	.31	2.88	1.23	93.90		4	25	30	.35		.14			
479.0	484.0	73784	5.0	.0	2E0	4.20	.21	2.93	1.50	30.50		4	25	30	.08		.14			
484.0	489.0	73785	5.0	.0	2E4	4.47	.14	2.75	3.05	17.80		4	25	30	2.33		.14			
489.0	494.0	73786	5.0	.0	2F4	4.48	.21	4.38	5.85	34.30		4	25	30	.05		.14			
494.0	499.0	73787	5.0	.0	2E0	4.66	.44	1.60	1.54	32.90		15	23	39	.07		.27			
499.0	504.0	73788	5.0	.0	2E0	4.26	.27	1.51	1.57	24.30		15	23	39	.08		.27			
504.0	509.0	73789	5.0	.0	2E81	3.92	.22	1.77	1.30	21.90		15	23	39	.06		.27			
509.0	514.0	73790	5.0	.0	2E81	3.83	.16	2.02	1.40	24.70		15	23	39	.07		.27			
514.0	519.0	73791	5.0	.0	2E0	4.31	.17	2.10	2.00	22.60		7	31	38	.07		.23			
519.0	524.0	73792	5.0	.0	2E0	4.36	.19	2.38	2.37	18.80		7	31	38	.10		.23			
524.0	529.0	73793	5.0	.0	2E8	4.62	.26	2.10	2.42	20.90		7	31	38	.03		.23			
529.0	534.0	73794	5.0	.0	2E8	4.34	.27	4.12	4.84	38.10		7	31	38	.10		.23			
534.0	539.0	73795	5.0	.0	2E0	4.61	.21	3.13	2.51	24.30		3	35	39	.04		.09			
539.0	544.0	73796	5.0	.0	2E0	4.82	.36	1.05	3.46	10.60		3	35	39	.04		.09			
544.0	549.0	73797	5.0	.0	2F0	4.51	.20	3.26	5.20	11.60		3	35	39	.03		.09			
549.0	554.0	73798	5.0	.0	2F0	4.98	.16	1.49	4.96	11.60		3	35	39	.04		.09			
554.0	559.0	73799	5.0	.0	2F0	4.73	.16	2.90	4.83	17.80		4	30	34	.04		.05			
559.0	564.0	73800	5.0	.0	2E4&	4.58	.15	3.10	6.30	14.00		4	30	34	.28		.05			
564.0	569.0	73801	5.0	.0	2D5	3.60	.13	2.66	4.95	18.90		4	30	34	.04		.05			

DDH: 76-22 UTM-N: 8799.1 UTM-E: 14227.3 UTM-ELEV: 4012.1 TOTAL DEPTH: 630.0 SECTION: 119+000
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

-----DEPTHS-----							-----ASSAYS-----													
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
504.0	509.0	73807	5.0	.0	2B49	3.71	.22	3.80	3.50	31.90		5	14	19	.07		.11			
509.0	514.0	73808	5.0	.0	2F4	3.77	.13	4.30	5.90	37.00		5	14	19	.07		.11			
514.0	519.0	73809	5.0	.0	2E46	3.26	.35	2.60	4.30	26.10		5	14	19	7.09		.11			
519.0	524.0	73810	5.0	.0	2G42	3.80	.13	7.50	8.50	49.00		5	14	19	7.91		.11			
524.0	529.0	73811	5.0	.0	2F4	4.04	.04	7.00	8.30	41.10		4	31	35	.02		.06			
529.0	532.4	73812	3.4	.0	2F4	5.08	.31	4.80	6.11	33.20		4	31	35	.14		.06			
548.0	553.0	73814	5.0	.0	2H49	4.33	.53	7.00	9.30	58.30		28	12	40	.02		.06			
553.0	558.0	73815	5.0	.0	2H49	4.57	.61	4.90	6.50	40.50		28	12	40	.07		.06			
558.0	563.0	73816	5.0	.0	2H49	4.49	.32	7.60	8.40	58.60		28	12	40	.02		.06			
563.0	568.0	73817	5.0	.0	2F49	4.81	.36	5.30	7.50	42.50		3	33	37	.03		.04			
568.0	573.0	73818	5.0	.0	2F4	4.58	.10	6.70	8.30	54.90		3	33	37			.04			
573.0	578.0	73819	5.0	.0	2F4	4.69	.13	6.50	9.90	49.00		3	33	37	.01		.04			
578.0	583.0	73820	5.0	.0	2F4	4.76	.22	4.70	7.00	39.10		3	33	37	.01		.04			
583.0	588.0	73821	5.0	.0	2F4	4.84	.11	5.00	5.70	54.50		9	25	34	.04		.10			
588.0	593.0	73822	5.0	.0	2E48	4.70	.20	4.00	3.30	68.60		9	25	34	.14		.10			
593.0	598.0	73823	5.0	.0	2H49	4.54	.32	4.70	7.80	61.00		9	25	34	.11		.10			
598.0	603.0	73824	5.0	.0	2D0	3.43	.18	2.40	6.30	44.60		9	25	34	.10		.10			
603.0	608.0	73825	5.0	.0	2D0	2.89	.08	1.50	3.90	26.40		4	2	6	.15		.04			
608.0	613.0	73826	5.0	.0	2A4	2.71	.10	2.50	3.20	48.70		4	2	6	.15		.04			
613.0	618.0	73827	5.0	.0	1D21	2.74	.06	.08	.01	2.60		4	2	6	.21		.04			
618.0	622.0	73828	4.0	.0	1D21	2.73	.16	.02	.01	4.00		4	2	6	.22		.04			
622.0	626.0	73829	4.0	.0	1D21	2.44	.13	.03	.01	3.50		4	1	5	.18		.06			
626.0	630.0	73830	4.0	.0	1D21	2.75	.08	.03	.18	1.50		4	1	5	.14		.06			

DDH: 77-01 UTM-N: 8573.3 UTM-E: 15213.8 UTM-ELEV: 4147.4 TOTAL DEPTH: 729.0 SECTION: 125
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

---DEPTHS---		-----ASSAYS-----																			
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
568.8	573.8	73906	5.0	.0	2G4	4.61	.14	4.39	4.35	65.10		.41	3	27	31	8.90		.16			
573.8	578.8	73907	5.0	.0	2G4	4.65	.13	6.28	6.48	83.80		.21	3	25	28	12.30		.12			
578.8	586.0	73908	7.2	.0	2E4	4.61	.11	1.76	2.80	19.00		.07	1	37	38	.10					
586.0	597.0	73909	11.0	.0	2E14	4.02	.02	2.02	3.49	21.00			2	32	34	.05					
597.0	601.0	73910	4.0	.0	2E1	3.55	.01	1.01	.49	11.40			1	29	30	.05					
601.0	607.0	73911	6.0	.0	2E1	3.07	.01	.01	.05	3.00			1	15	17	.05		.01			
607.0	612.0	73912	5.0	.0	2C3	3.70	.23	.97	2.85	33.40			5	20	26	.05		.07			
612.0	617.0	73913	5.0	.0	2C3	3.78	.26	.01	.68	7.00			5	24	29	.10		.08			
617.0	622.0	73914	5.0	.0	2E1	3.92	.48	.96	1.63	13.30			6	27	33	.10		.22			
622.0	627.0	73915	5.0	.0	2E1	3.98	.28	.30	1.44	5.00			6	28	35	.05		.14			
627.0	632.0	73916	5.0	.0	2E1	3.98	.22	1.43	2.32	8.70			6	26	33	.10		.16			
632.0	637.0	73917	5.0	.0	2E1	3.92	.50	.49	1.09	7.70			4	28	33	.05		.80			
637.0	642.0	73918	5.0	.0	2E1	3.82	.58	.27	.94	10.00			7	25	32	.05		.13			
642.0	647.0	73919	5.0	.0	2E84	4.08	.33	1.57	2.70	12.00		.07	6	27	34	.05		.18			
647.0	652.0	73920	5.0	.0	2E8	4.10	.29	1.17	2.20	8.70		.01	8	28	36	.05		.23			
652.0	657.0	73921	5.0	.0	2C2	3.88	.22	.27	1.04	5.60		.27	2	26	29	.05		.05			
657.0	662.0	73922	5.0	.0	2E8	4.35	.34	.92	1.95	7.30		.01	8	30	38	.05		.14			
662.0	667.0	73923	5.0	.0	2E1	3.75	.47	1.06	1.68	8.70		.07	5	23	29	.05		.13			
667.0	672.0	73924	5.0	.0	2E1	3.83	.22	.10	1.66	3.70			5	26	32	.05		.12			
672.0	675.0	73925	3.0	.0	2E1	4.01	.28	.04	1.34	4.40			5	30	36	.05		.12			
675.0	685.0	73926	10.0	.0	2F0	4.10	.31	1.44	4.33	8.00			5	29	35	.05		.09			
685.0	690.0	73927	5.0	.0	1D4	3.83	.12	1.42	5.38	13.30			6	22	28	.05		.09			

DDH: 77-02 UTM-N: 8468.9 UTM-E: 15315.3 UTM-ELEV: 4140.9 TOTAL DEPTH: 732.0 SECTION: 126
 RFE: S2 RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

---DEPTHS---		SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	ASSAYS														S.G. W.R.
FROM	TO					Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	
474.0	476.0	73933	2.0	.0 2G24	4.41	.22	6.72	6.07	92.00		.27	12	14	26	10.80		.23			
476.0	478.0	73934	2.0	.0 2E4	4.63	.24	4.66	3.50	54.70		.41	10	25	36	1.30		.26			
478.0	484.0	73935	6.0	.0 2EG4	4.69	.12	5.63	5.16	71.40		.41	4	23	28	12.90		.14			
484.0	488.0	73936	4.0	.0 2E1	4.81	.22	1.58	2.25	22.30		.01	2	37	40	1.70		.01			
488.0	490.3	73937	2.3	.0 2EG	4.61	.06	2.50	4.78	25.70			2	32	34	6.20		.01			
490.3	491.3	73938	1.0	.0 2G4	4.55	.20	4.25	7.66	39.00		.07	2	20	23	17.00		.01			
491.3	497.6	73939	6.3	.0 2E14	3.94	.26	2.21	2.80	27.70		.07	3	31	34	.10		.05			
497.6	498.4	73940	.8	.0 2G4	4.52	.02	3.55	7.02	38.70		.07	2	26	28	12.30		.01			
498.4	499.6	73941	1.2	.0 2E4	4.81	.11	1.89	2.20	19.00		.07	1	40	41	.20		.01			
499.6	503.0	73942	3.4	.0 2G14	4.88	.05	4.78	8.26	44.10		.07	2	22	25	18.50		.01			
503.0	505.0	73943	2.0	.0 2C0	4.20	.08	.80	1.50	9.60		.07	2	33	35	.10					
505.0	510.5	73944	5.5	.0 2F4	4.65	.18	6.38	8.46	74.70		.55	2	31	33	.05		.01			
510.5	515.0	73945	4.5	.0 2F4	4.67	.29	5.78	7.98	47.70		.14	2	32	34	.05		.01			
515.0	520.0	73946	5.0	.0 2E4	4.98	.09	4.91	6.60	47.40		.21	2	34	36	.10		.01			
520.0	526.4	73947	6.4	.0 2E0	3.75	.01	.44	.11	6.30		.14	1	27	29	.05					
526.4	531.0	73948	4.6	.0 2E4	4.02	.11	2.30	2.52	26.00		.01	2	31	33	.05		.05			
531.0	535.0	73949	4.0	.0 2F24	4.65	.06	4.90	5.03	42.00		.07	2	35	38	.05		.01			
535.0	539.0	73950	4.0	.0 2E1	4.02	.01	.21	.10	5.00		.07	1	31	32	.05					
539.0	543.9	73951	4.9	.0 2E4	4.44	.08	4.27	6.89	24.00		.07	2	32	35	.05		.02			
543.9	548.3	73952	4.4	.0 2C0	3.56	.16	.21	.08	5.40		.07	1	24	26	1.30		.01			
548.3	552.0	73953	3.7	.0 2E4	4.69	.04	3.30	7.35	22.70		.62	2	27	30	11.20		.01			
552.0	556.8	73954	4.8	.0 2E4	4.59	.05	4.41	6.05	26.70		.27	2	34	37	2.60		.01			
556.8	561.0	73955	4.2	.0 2F2	4.37	.03	15.05	15.00	59.70		.14	3	23	27	.05		.01			
561.0	563.0	73956	2.0	.0 2H9	3.75	.66	4.72	9.29	43.00		.48	22	3	26	.10		.08			
563.0	568.0	73957	5.0	.0 2C8	4.17	.28	.54	1.91	10.30		.21	5	30	35	.05		.09			
568.0	572.0	73958	4.0	.0 2C0	3.82	1.02	1.91	1.12	29.40		.14	4	29	34	.05		.08			
572.0	577.0	73959	5.0	.0 2C0	3.65	.46	.36	.50	10.00		.01	5	30	36	.05		.07			
577.0	582.0	73960	5.0	.0 2C0	3.64	.59	.88	1.60	15.40		.01	5	23	29	.05		.11			
582.0	588.5	73961	6.5	.0 2E1	4.18	.27	1.55	3.05	16.60		.01	6	29	35	.05		.20			
588.5	593.5	73962	5.0	.0 2EC	4.09	.27	1.86	2.95	17.70		.01	6	25	31	.05		.26			
593.5	600.5	73963	7.0	.0 2C8	3.82	.67	.67	1.28	23.40		.07	6	21	28	.05		.15			
600.5	602.5	73964	2.0	.0 2E1	4.41	.26	1.81	3.27	13.00		.07	7	32	39	.05		.18			
602.5	607.0	73965	4.5	.0 2CE	4.20	.41	.47	1.11	16.60			4	31	36	.05		.08			
607.0	612.0	73966	5.0	.0 2C0	3.55	.30	.37	.87	9.30			5	30	35	.10		.07			
612.0	618.5	73967	6.5	.0 2C0	4.29	.30	.46	1.52	7.70			3	30	34	.10		.11			
618.5	620.5	73968	2.0	.0 2F0	4.44	.12	7.50	13.90	28.70		.07	6	24	30	.05		.21			
620.5	626.5	73969	6.0	.0 2D0	3.68	.26	1.37	2.76	11.00			3	23	27	.05		.11			
626.5	633.0	73970	6.5	.0 2C0	3.70	.29	.26	1.46	10.70			5	25	31	.05		.13			
633.0	636.5	73971	3.5	.0 2E1	3.77	.27	.06	1.22	3.00		.03	4	26	31	.05		.10			
636.5	639.5	73972	3.0	.0 2C0	3.85	.17	.05	1.92	3.30		.03	3	29	32	.05		.06			
639.5	645.0	73973	5.5	.0 2E1	4.44	.30	.17	1.76	4.40		.03	7	34	41	.05		.10			
645.0	650.0	73974	5.0	.0 2E1	4.57	.55	.38	1.60	6.00		.03	6	38	44	.10		.12			
650.0	655.0	73975	5.0	.0 2E4	4.50	.40	1.66	2.56	10.00		.01	7	35	43	.05		.11			
655.0	658.5	73976	3.5	.0 2F4	4.39	.06	6.73	14.10	30.10		.01	3	27	31	.05		.04			
658.5	660.0	73977	1.5	.0 2D4	3.77	.12	4.95	14.10	30.10		.07	5	17	23	.05		.05			
660.0	667.5	73978	7.5	.0 2F4	4.69	.05	4.61	9.80	22.40		.07	2	35	38	.05		.01			
667.5	673.0	73979	5.5	.0 2D4	3.60	.06	7.38	17.00	28.70		.07	5	9	15	.05		.04			
673.0	678.0	73980	5.0	.0 2F14	3.80	.05	8.12	23.00	41.70		.07	4	8	12	.05		.02			
678.0	683.0	73981	5.0	.0 2F14	3.56	.06	7.50	21.00	36.00		.14	6	9	15	.05		.04			
683.0	687.0	73982	4.0	.0 2F14	3.64	.08	6.48	17.70	35.00			7	12	19	.05		.06			
687.0	689.0	73983	2.0	.0 2H84	3.57	.25	5.41	16.40	29.70		.21	9	10	20	.05		.04			

DDH: 77-02 UTM-N: 8468.9 UTM-E: 15315.3 UTM-ELEV: 4140.9 TOTAL DEPTH: 732.0 SECTION: 126
RFE: S2 RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS----				-----ASSAYS-----																
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
689.0	690.7	73984	1.7	.0 2F14	3.91	.22	6.33	16.70	52.30		.21	10	11	21	.05		.10			
690.7	695.5	73985	4.8	.0 2C0	3.34	.89	.35	1.08	40.00			9	10	20	.10		.11			
695.5	700.5	73986	5.0	.0 2C0	3.24	.52	.14	1.24	40.70			9	11	20	.10		.06			

DDH: 77-03 UTM-N: 8380.4 UTM-E: 15406.4 UTM-ELEV: 4118.9 TOTAL DEPTH: 694.0 SECTION: 127
RFE: S2 RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
520.5	525.0	73992	4.5	.0	2F4	4.12	.10	4.30	9.80	31.10		.21	7	22	30	.05		.02			
525.0	530.0	73993	5.0	.0	2D4	3.88	.05	3.81	6.30	35.60		.34	4	25	29	.05		.04			
530.0	535.0	73994	5.0	.0	2E1	4.12	.20	.35	1.22	10.20			3	32	35	.05		.03			
535.0	540.0	73995	5.0	.0	2E1	4.03	.33	.11	.51	10.20			5	30	35	.05		.05			
540.0	545.0	73996	5.0	.0	2E4	3.97	.21	2.30	2.07	16.50		.14	1	29	31	.05		.01			
545.0	550.0	73997	5.0	.0	2E1	3.80	.07	.13	1.50	7.30			2	27	30	.05		.02			
550.0	555.0	73998	5.0	.0	2E1	3.83	.24	.33	.87	14.30			2	27	30	.05		.02			
555.0	560.0	73999	5.0	.0	2E1	3.94	.28	.64	.70	9.70			2	30	33	.05		.03			
560.0	566.0	74000	6.0	.0	2E1	4.02	.20	.91	1.28	21.50			3	30	33	.05		.04			
567.0	572.0	74002	5.0	.0	2E1	4.12	.23	.77	1.06	20.40			3	32	35	.05		.03			
572.0	577.0	74003	5.0	.0	2E1	3.95	.13	.81	2.46	9.70		.14	5	28	34	.05		.05			
577.0	582.0	74004	5.0	.0	2E1	4.08	.12	1.04	2.18	16.70		.27	5	31	36	.05		.06			
582.0	586.0	74005	4.0	.0	2E8	4.39	.20	.89	1.21	12.00		.99	7	32	40	.05		.10			
586.0	591.0	74006	5.0	.0	2E8	3.55	.21	1.66	2.84	22.40		.41	4	20	25	.05		.09			
591.0	595.0	74007	4.0	.0	2E1	3.97	.16	.52	2.18	6.00		.07	5	28	33	.05		.09			
595.0	598.0	74008	3.0	.0	2E1	4.22	.28	.01	.91	5.30			3	33	37	.05		.09			
598.0	603.0	74009	5.0	.0	2E1	3.77	.32	.06	.80	6.30			2	29	32	.05		.03			
603.0	609.0	74010	6.0	.0	2E1	3.78	.35	.12	.60	62.90			2	25	28	.05		.02			
609.0	615.0	74011	6.0	.0	2E1	3.97	.25	.23	.63	7.20			3	27	30	.05		.03			
615.0	621.0	74012	6.0	.0	2D4	3.51	.05	3.56	8.98	17.00			4	15	19	.10		.03			
621.0	627.0	74013	6.0	.0	2C0	2.81	.11	.96	2.14	10.40		.21	4	6	11	.10		.02			
627.0	635.0	74014	8.0	.0	2D4	3.39	.09	4.38	13.20	40.90		.07	7	6	13	.10		.03			
635.0	638.0	74015	3.0	.0	0Q9	2.96	.04	2.13	1.93	41.20		.89	2	3	6	.10		.04			

DDH: 77-07 UTM-N: 8060.0 UTM-E: 15635.9 UTM-ELEV: 4101.6 TOTAL DEPTH: 604.0 SECTION: 130
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	ASSAYS													
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %
368.4	369.7	74031	1.3	.0	2E8	4.26	.12	4.95	3.24	100.00		.69	4	20	25	5.07		.20		
369.7	375.0	74032	5.3	.0	2E8	4.95	.20	1.85	2.15	28.00		.82	12	27	40	.18		.62		
375.0	380.0	74033	5.0	.0	2E0	4.13	.17	1.22	1.06	17.20			5	28	33	.11		.16		
380.0	385.0	74034	5.0	.0	2E1	4.48	.02	1.07	1.03	11.40			2	36	38	.07		.04		
385.0	390.0	74035	5.0	.0	2C3	4.07	.01	.51	.42	8.60			1	30	32	.08		.03		
390.0	395.0	74036	5.0	.0	2C3	3.44	.01	.46	.31	9.30			1	20	22	.08		.01		
395.0	400.0	74037	5.0	.0	2E1	3.17	.01	.47	.44	7.60			1	32	34	.08		.02		
400.0	407.5	74038	7.5	.0	2C3	3.67	.04	.18	.23	6.30			1	27	28	.08		.01		
407.5	412.0	74039	4.5	.0	0Q0	3.18	.21	.66	.12	48.00			1	12	14	.08		.01		
412.0	415.6	74040	3.6	.0	2C3	3.97	.03	1.22	1.57	11.70		.21	1	30	31	.11		.01		
415.6	419.5	74041	3.9	.0	2F4	4.65	.13	6.60	10.00	63.40		.21	2	31	34	.20		.06		
419.5	425.0	74042	5.5	.0	2E4	4.08	.12	3.20	5.20	27.00		.14	2	27	29	.23		.03		
425.0	430.0	74043	5.0	.0	2E1	3.89	.13	.88	1.04	11.40		.34	1	32	33	.20		.01		
430.0	434.0	74044	4.0	.0	2C3	3.98	.10	.96	1.30	9.70		.14	1	30	31	.21		.02		
434.0	439.0	74045	5.0	.0	2E4	3.70	.44	3.45	2.17	29.40		.21	1	27	28	.07		.01		
439.0	443.4	74046	4.4	.0	2E4	4.31	.11	3.62	5.22	25.10		.07	1	31	32	.08		.01		
443.4	447.0	74047	3.6	.0	2F4	4.78	.03	10.05	13.20	67.60		.62	1	28	30	.06		.03		
447.0	452.0	74048	5.0	.0	2D4	3.53	.17	4.08	7.56	25.30		.14	3	17	20	.15		.23		
452.0	457.2	74049	5.2	.0	2DE	3.75	.14	2.20	4.20	14.60		.21	2	22	25	.11		.07		
457.2	458.7	74050	1.5	.0	2F4	4.20	.07	6.75	13.40	32.10		.41	4	23	27	.11		.21		
458.7	462.7	74051	4.0	.0	2D8	4.05	.31	7.25	8.95	41.60		.21	6	19	25	.12		.50		
462.7	466.0	74052	3.3	.0	2D8	4.10	.53	2.68	4.40	20.20			4	26	30	.15		.25		
466.0	471.0	74053	5.0	.0	2E1	4.13	.40	.41	.74	14.50			2	32	35	.03		.05		
471.0	477.3	74054	6.3	.0	2E1	3.98	.38	.50	.67	7.00			2	32	34	.04		.03		
477.3	482.0	74055	4.7	.0	2E1	4.17	.39	.99	1.60	7.80		.07	6	29	35	.08		.11		
482.0	487.0	74056	5.0	.0	2E8	4.12	.29	1.50	1.88	12.10		.01	7	30	38	.10		.24		
487.0	492.4	74057	5.4	.0	2E8	4.63	.29	.47	1.78	5.00			7	33	40	.11		.20		
496.6	502.2	74059	5.6	.0	2D3	3.71	.13	1.95	4.48	12.30		1.03	2	18	21	.11		.05		
502.2	506.0	74060	3.8	.0	2C3	4.37	.23	.10	1.18	3.40			5	29	34	.07		.18		
506.0	510.0	74061	4.0	.0	2C3	4.38	.31	.05	.89	3.90			2	29	32	.07		.10		
510.0	515.0	74062	5.0	.0	2C3	4.33	.68	.60	1.20	6.80			3	29	32	.10		.09		
515.0	518.0	74063	3.0	.0	2C3	4.28	.14	.82	1.89	5.40		.01	4	28	32	.12		.12		
518.0	522.2	74064	4.2	.0	2C3	4.42	.22	1.64	2.27	7.30		.01	4	28	32	.12		.12		
522.2	527.2	74065	5.0	.0	2C3	4.44	.50	.06	1.04	5.10		.01	1	32	34	.04		.03		
527.2	531.5	74066	4.3	.0	2C3	4.45	.20	1.45	2.90	5.80		.01	4	29	33	.06		.12		
531.5	537.3	74067	5.8	.0	2D4	3.91	.12	3.11	7.40	10.00		.01	3	21	25	.06		.04		
537.3	542.0	74068	4.7	.0	2D0	3.22	.10	2.09	4.60	23.40		.14	4	4	9	.27		.06		
542.0	551.0	74069	9.0	.0	2B0	2.72	.04	.96	2.18	13.10		.14	2	2	4	.27		.04		
551.0	556.0	74070	5.0	.0	2B0	2.84	.04	.94	2.01	11.00		.07	1	3	4	.64		.01		
556.0	561.0	74071	5.0	.0	2B0	2.82	.04	1.12	2.23	12.30			1	2	3	.58		.01		
561.0	566.0	74072	5.0	.0	2B5	2.50	.06	.89	2.28	13.00		.14	1	1	3	.49		.01		
566.0	571.0	74073	5.0	.0	2B0	2.79	.11	.68	2.08	12.40		.14	3	2	5	.37		.01		
571.0	577.0	74074	6.0	.0	2B0	2.71	.08	1.34	3.20	26.80		.27	2	1	3	.32		.02		
577.0	582.2	74075	5.2	.0	2B0	2.86	.09	.67	2.20	9.80		.14	2	2	5	.61		.04		
582.2	584.3	74076	2.1	.0	1D4	2.81	.05	.19	.23	2.80			3	3	6	.41		.13		
584.3	587.0	74077	2.7	.0	1D4	2.82	.02	.04	.07	1.10			3	1	4	.32		.12		
587.0	590.8	74078	3.8	.0	2A0	2.40	.01	.01	.05	1.20			3	1	4	.28		.17		
590.8	594.8	74079	4.0	.0	2B0	2.72	.03	.02	.10	2.60			2	1	4	.27		.10		
594.8	598.0	74080	3.2	.0	1D4	2.73	.05	.02	.11	3.90			2	1	3	.30		.07		

DDH: 77-09 UTM-N: 8363.5 UTM-E: 14986.3 UTM-ELEV: 4096.7 TOTAL DEPTH: 765.0 SECTION: 125
RFE: S2 RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	---ASSAYS---													
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %
516.8	520.8	74088	4.0	.0	2D0	3.34	.18	5.83	2.60	78.60		.96	2	9	12	.30		.03		
520.8	525.0	74089	4.2	.0	2G4	4.32	.06	3.52	10.30	34.10		.01	2	18	21	8.48		.03		
525.0	531.0	74090	6.0	.0	2G4	4.78	.03	2.12	4.46	19.80		.07	1	30	31	12.95		.02		
531.0	537.0	74091	6.0	.0	2G4	4.89	.09	3.95	6.62	37.90		.01	1	21	23	18.80		.06		
537.0	542.5	74093	5.5	.0	2D0	4.02	.17	1.83	3.40	24.00		.01	1	24	25	3.94		.03		
542.5	548.0	74094	5.5	.0	2D0	4.31	.08	2.82	5.63	44.00		.14	3	24	27	6.00		.09		
577.0	578.0	74096	1.0	.0	2H14	5.11	.03	2.42	5.96	32.10		.07	2	37	40	.20		.04		
578.0	581.3	74097	3.3	.0	2H2	4.61	.33	1.41	2.34	23.40		.01	29	15	45	.17		.10		
581.3	586.9	74098	5.6	.0	2C0	4.08	.05	1.40	.38	13.70		.07	2	31	33	.04		.04		
586.9	591.3	74099	4.4	.0	2E0	4.74	.19	1.02	1.19	15.60		.07	3	37	41	.05		.12		
591.3	596.3	74100	5.0	.0	2E8	4.75	.14	.76	1.36	9.50		.07	5	37	42	.02		.14		
596.3	599.3	74101	3.0	.0	2F0	4.82	.13	3.34	3.95	31.90		.07	4	36	40	.02		.09		
599.3	602.4	74102	3.1	.0	2F4	4.92	.06	6.00	12.30	45.30		.07	2	32	35	.02		.04		
602.4	607.4	74103	5.0	.0	2E34	5.00	.08	3.46	6.75	22.90		.07	2	37	40	.02		.04		
607.4	611.6	74104	4.2	.0	2E3	4.83	.26	2.78	4.14	21.60		.07	3	37	41	.02		.09		
611.6	616.6	74105	5.0	.0	2D3	4.30	.20	2.62	2.48	20.90		.07	3	31	35	.03		.09		
616.6	619.3	74106	2.7	.0	2E34	4.86	.09	2.46	3.90	19.60		.01	3	38	41	.03		.07		
619.3	623.3	74107	4.0	.0	2F4	4.91	.14	5.13	8.80	48.00		.06	3	32	35	.02		.13		
623.3	626.5	74108	3.2	.0	2F4	5.00	.11	4.50	6.86	31.20		.06	3	34	38	.03		.11		
626.5	630.0	74109	3.5	.0	2E4	4.54	.24	4.95	8.38	47.90			5	29	34	.04		.13		
630.0	634.5	74110	4.5	.0	2E4	4.36	.29	2.20	2.54	25.00			4	32	37	.05		.16		
634.5	639.0	74111	4.5	.0	2E4	4.63	.33	2.79	3.38	26.90			5	30	36	.05		.26		
639.0	642.0	74112	3.0	.0	2E4	4.74	.25	3.26	5.68	21.00			7	30	38	.03		.33		
642.0	646.9	74113	4.9	.0	2E4	4.65	.22	2.70	4.67	19.70			6	30	37	.04		.29		
646.9	650.0	74114	3.1	.0	2E4	4.14	.16	1.64	4.43	11.80		.03	6	27	33	.04		.20		
650.0	654.0	74115	4.0	.0	2E4	4.09	.34	1.38	4.20	12.70		.07	8	25	34	.03		.26		
654.0	657.5	74116	3.5	.0	2E34	4.29	.12	2.68	8.14	11.30		.07	7	26	33	.02		.24		
657.5	661.3	74117	3.8	.0	2E34	4.63	.12	3.88	7.60	12.00		.01	5	30	35	.02		.20		
661.3	666.3	74118	5.0	.0	2E34	5.05	.15	3.24	5.17	12.90		.07	1	39	40	.01		.02		
666.3	671.3	74119	5.0	.0	2E34	4.85	.13	3.86	5.56	18.20		.07	1	38	40	.04		.03		
671.3	675.3	74120	4.0	.0	2E34	4.78	.18	2.91	4.41	13.10		.01	1	40	41	.03		.02		
675.3	678.9	74121	3.6	.0	2E34	4.42	.08	2.41	4.47	12.50		.07	1	36	38	.07		.02		
678.9	683.9	74122	5.0	.0	2D0	3.19	.20	2.68	4.44	25.20		.14	7	9	16	.41		.06		
683.9	688.9	74123	5.0	.0	2D0	3.36	.40	2.69	6.73	29.60		.21	9	9	18	.41		.05		
688.9	692.5	74124	3.6	.0	2D0	3.36	.18	2.81	4.66	28.40		.14	7	16	24	.16		.06		

DDH: 77-10 UTM-N: 8165.0 UTM-E: 15223.0 UTM-ELEV: 4061.6 TOTAL DEPTH: 662.0 SECTION: 127
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	ASSAYS														
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
400.3	405.2	74129	4.9	.0	2C0	3.23	.11	.02	.15	5.40				2 19	21	.15		.03			
405.2	408.0	74130	2.8	.0	2E0	4.55	.14	.01	.05	6.10				4 39	44	.03		.06			
408.0	412.0	74131	4.0	.0	2A0	2.99	.19	.07	.51	5.50				3 13	16	.10		.07			
412.0	416.0	74132	4.0	.0	2A0	3.22	.20	.36	.68	7.40				3 18	21	.09		.07			
416.0	419.0	74133	3.0	.0	2A0	3.14	.34	.12	.26	5.20				1 19	20	.09		.02			
419.0	421.0	74134	2.0	.0	2A0	3.68	.27	.37	3.97	7.80				1 20	21	.04		.02			
421.0	422.0	74135	1.0	.0	2E4	4.22	.05	2.72	6.55	19.70		.01	1 33	34	.43			.02			
432.0	436.0	74137	4.0	.0	2G4	4.61	.06	6.28	10.20	114.10		.41	2 16	19	20.97			.09			
436.0	440.0	74138	4.0	.0	2G4	4.39	.07	5.32	9.20	83.70		.21	2 17	20	20.87			.11			
440.0	444.0	74139	4.0	.0	2G4	4.48	.05	4.49	8.32	59.40		.07	2 12	14	26.21			.08			
444.0	448.0	74140	4.0	.0	2G4	4.31	.06	6.46	8.86	73.60		.01	2 11	13	28.58			.07			
448.0	452.0	74141	4.0	.0	2G4	4.33	.05	5.80	10.30	68.60		.01	2 8	10	32.28			.04			
452.0	456.5	74142	4.5	.0	2G4	4.39	.05	6.21	9.47	76.70		.01	2 9	11	31.00			.04			
456.5	462.0	74143	5.5	.0	2G4	4.35	.07	6.70	9.72	77.70		.07	2 9	12	30.69			.04			
462.0	464.5	74144	2.5	.0	2E4	4.65	.08	10.10	3.72	124.50		.01	4 31	36	.61			.04			
464.5	465.5	74145	1.0	.0	2J4	4.18	.29	5.30	8.78	76.80		.07	10 20	31	4.09			.14			
465.5	467.0	74146	1.5	.0	2J4	4.29	.19	8.97	13.60	134.70		.34	10 12	23	9.98			.28			
467.0	468.5	74147	1.5	.0	2J4	2.96	.04	11.00	16.40	218.90		.48	5 20	25	.49			.30			
468.5	473.0	74148	4.5	.0	1D4	3.00	.10	1.20	2.10	30.50		.01	5 7	12	6.00			.11			
473.0	478.0	74149	5.0	.0	1D4	2.92	.11	.18	.23	5.40			4 3	8	5.31			.09			
478.0	480.0	74150	2.0	.0	1D4	3.39	.44	.48	.89	24.40			6 6	12	10.83			.11			
480.0	484.0	74151	4.0	.0	2E0	4.72	.11	2.04	.71	44.00		.14	4 39	43	.56			.07			
484.0	488.0	74152	4.0	.0	2E1	4.41	.19	.42	.19	10.50		.07	6 34	41	.10			.08			
488.0	492.0	74153	4.0	.0	2E1	4.03	.34	1.66	2.39	35.30			13 24	37	.05			.35			
492.0	496.0	74154	4.0	.0	2E1	4.31	.39	1.81	2.25	26.40		.14	10 26	37	.10			.18			
496.0	501.5	74155	5.5	.0	2E0	4.61	.24	.64	1.30	11.30		.07	5 35	41	.03			.14			
501.5	507.0	74156	5.5	.0	2E4	4.85	.09	2.50	4.53	21.40		.07	2 39	42	.02			.04			
507.0	511.0	74157	4.0	.0	2F4	5.08	.04	7.75	10.20	56.80		.01	2 34	36	.02			.01			
511.0	515.0	74158	4.0	.0	2F4	5.05	.10	5.87	9.68	47.50		.07	3 34	37	.02			.05			
515.0	518.0	74159	3.0	.0	2F4	4.74	.11	5.63	6.90	67.10		.07	4 34	38	.03			.18			
518.0	522.0	74160	4.0	.0	2E0	4.44	.35	3.02	1.80	35.40		.14	6 33	40	.03			.27			
522.0	524.0	74161	2.0	.0	2E0	4.95	.15	1.77	.88	55.90		.07	2 23	26	.02			.05			
524.0	525.0	74162	1.0	.0	2H0	4.35	.12	1.88	1.82	27.50		.07	12 25	38	.06			.10			
525.0	528.0	74163	3.0	.0	2E4	4.39	.15	4.43	3.41	60.80		.34	6 29	36	.04			.14			
528.0	531.0	74164	3.0	.0	2FE	4.87	.12	4.05	5.61	48.50		.34	4 33	37	.09			.10			
531.0	534.0	74165	3.0	.0	2E0	4.47	.10	1.08	2.64	18.10		.27	4 33	37	.02			.10			
534.0	537.0	74166	3.0	.0	2E4	4.09	.07	3.04	4.11	36.10		.41	2 28	31	.05			.05			
537.0	542.6	74167	5.6	.0	2E4	4.78	.07	3.24	3.92	28.40		.21	2 38	41	.03			.05			
542.6	546.5	74168	3.9	.0	2E4	4.61	.07	3.32	5.48	29.30		.07	1 35	36	.03			.03			
546.5	550.5	74169	4.0	.0	2E1	4.63	.11	2.10	2.22	17.80		.14	3 35	39	.04			.09			
550.5	554.5	74170	4.0	.0	2E8	4.26	.13	.94	1.90	10.10		.07	6 29	35	.03			.17			
554.5	559.5	74171	5.0	.0	2F4	4.44	.09	4.20	10.00	18.20		.55	4 29	33	.02			.14			
559.5	564.5	74172	5.0	.0	2F0	4.39	.10	2.23	6.11	9.00		.07	5 30	35	.03			.15			
564.5	566.5	74173	2.0	.0	2E1	3.95	.20	.21	2.19	4.80			4 29	33	.02			.09			
566.5	572.0	74174	5.5	.0	2E1	4.11	.13	.38	1.54	4.20			5 27	33	.02			.11			
572.0	577.0	74175	5.0	.0	2E1	4.26	.11	.61	2.25	5.00		.21	5 30	35	.07			.11			
577.0	582.0	74176	5.0	.0	2FE4	4.50	.08	4.41	11.10	13.50		.14	2 30	32	.03			.04			
582.0	587.0	74177	5.0	.0	2F4	5.08	.07	5.31	9.60	17.70		.07	2 34	36	.02			.03			
587.0	592.0	74178	5.0	.0	2F4	5.21	.01	6.38	10.40	23.40		.07	1 34	36	.01			.02			
592.0	597.0	74179	5.0	.0	2F4	5.78	.03	4.07	7.23	14.80		.07	1 37	38	.01			.01			

DDH: 77-10 UTM-N: 8165.0 UTM-E: 15223.0 UTM-ELEV: 4061.6 TOTAL DEPTH: 662.0 SECTION: 127
RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
597.0	609.0	74180	12.0	.0	2F4	4.88		4.46	10.10	21.90		.01	2	31	33	.02		.02			
609.0	614.0	74181	5.0	.0	2D4	3.38	.05	3.72	9.85	27.20		.14	6	7	14	.30		.04			
614.0	619.0	74182	5.0	.0	2D4	3.51	.10	3.00	7.68	24.00		.07	11	8	20	.11		.02			
619.0	623.0	74183	4.0	.0	2C0	3.08	.06	1.36	2.27	16.20		.14	5	5	10	.29		.02			
623.0	625.6	74184	2.6	.0	2C0	2.92	.56	.60	1.94	37.90		.07	6	4	10	.18		.05			
625.6	628.0	74185	2.4	.0	1E0	2.77	.39	.22	.50	19.70			3	2	5	.25		.03			

DDH: 77-12 UTM-N: 7802.6 UTM-E: 15208.3 UTM-ELEV: 4014.7 TOTAL DEPTH: 402.0 SECTION: 129
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	ASSAYS														
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
228.2	231.2	74191	3.0	.0	2C3	3.55	.10	.30	.54	5.40			2	22	24	.23		.04			
231.2	234.7	74192	3.5	.0	2AE4	4.08	.04	1.70	5.88	8.60		.21	2	28	30	.03		.03			
234.7	237.3	74193	2.6	.0	2A4	3.54	.05	4.23	10.50	25.10		.41	2	14	16	.11		.02			
237.3	241.0	74194	3.7	.0	2A4	3.55	.05	3.46	13.73	20.40		.34	3	13	16	.11		.03			
241.0	244.0	74195	3.0	.0	2D0	3.53	.06	1.85	7.25	22.30		.48	3	16	19	.37		.05			
244.0	247.3	74196	3.3	.0	2GH	4.49	.32	6.58	6.00	39.90		.41	14	17	32	7.82		.49			
247.3	250.6	74197	3.3	.0	2G4	3.98	.17	10.35	5.52	51.00		.48	9	10	20	3.58		.36			
250.6	253.6	74198	3.0	.0	2F4	4.55	.14	8.28	7.00	51.30		.34	9	21	31	5.49		.49			
253.6	257.0	74199	3.4	.0	2B0	3.04	.14	.90	1.55	11.30		.07	5	3	8	7.36		.15			
257.0	258.0	74200	1.0	.0	2G84	4.68	.08	7.04	6.00	64.20		.21	9	23	33	7.38		.58			
258.0	259.7	74201	1.7	.0	2GH4	4.53	.28	5.31	5.27	83.50		.14	24	6	30	12.08		.59			
259.7	263.5	74202	3.8	.0	2A4	3.10	.08	2.57	2.74	26.60		.07	6	4	11	3.20		.22			
263.5	271.7	74203	8.2	.0	2B0	2.92	.03	.20	.54	1.50		.07	3	3	7	7.25		.07			
271.7	275.7	74204	4.0	.0	2D0	3.56	.14	2.29	6.94	35.10		.07	9	14	24	1.56		.10			
275.7	280.5	74205	4.8	.0	2D0	3.21	.16	1.86	4.75	26.10		.01	7	10	18	.59		.05			
280.5	286.0	74206	5.5	.0	2F0	5.21	.10	3.05	5.15	22.00		.01	2	37	39	.05		.04			
286.0	290.3	74207	4.3	.0	2H4	4.48	.58	4.82	7.46	48.70		.01	21	16	38	.04		.11			
290.3	292.4	74208	2.1	.0	2F84	4.74	.13	5.73	9.85	55.10		.01	6	29	36	.03		.09			
292.4	297.4	74209	5.0	.0	2D0	2.82	.10	.71	4.30	13.60		.07	6	4	10	.38		.06			
297.4	302.4	74210	5.0	.0	2D0	2.76	.08	1.81	2.54	33.40		.01	4	3	8	.51		.04			
302.4	307.0	74211	4.6	.0	2D0	2.82	.10	1.58	3.64	29.20		.07	7	2	9	.55		.03			
307.0	310.0	74212	3.0	.0	2D0	3.08	.13	1.96	7.08	36.30		.07	13	1	15	.26		.03			
310.0	315.0	74213	5.0	.0	2H4	4.18	.55	2.91	7.40	50.80		.07	46		46	.03		.03			
315.0	319.7	74214	4.7	.0	2H4	4.10	.56	2.16	5.26	35.20		.07	49		49	.03		.03			
319.7	321.0	74215	1.3	.0	2D0	3.17	.32	2.96	5.05	56.90		.07	19		19	.15		.04			
321.0	324.0	74216	3.0	.0	2H0	4.14	.52	.32	.55	8.60		.27	47		47	.04		.02			
324.0	329.0	74217	5.0	.0	2D0	3.20	.17	.84	5.54	13.80		.14	17	4	21	.17		.03			
329.0	334.0	74218	5.0	.0	2D0	3.15	.10	1.57	4.97	27.20		.07	14	1	16	.45		.02			
334.0	339.0	74219	5.0	.0	2D0	3.06	.13	3.66	5.64	60.30		.07	11	20	31	.56		.03			
339.0	344.0	74220	5.0	.0	2A0	2.71	.08	.87	2.69	21.20		.07	5	3	9	.50		.02			
344.0	349.0	74221	5.0	.0	2A4	2.78	.07	1.54	2.83	39.50		.21	7	2	10	.54		.01			
349.0	354.0	74222	5.0	.0	2A0	2.89	.05	1.04	2.69	23.90		.14	3	4	7	.37					
354.0	359.5	74223	5.5	.0	2A4	2.66	.05	1.75	2.79	27.40		.21	2	1	3	.47		.01			

DDH: 77-13 UTM-N: 7974.9 UTM-E: 14986.7 UTM-ELEV: 4018.2 TOTAL DEPTH: 543.0 SECTION: 127
RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	ASSAYS														
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
376.0	380.0	74229	4.0	.0	2C0	3.35	.26	.02	.09	7.90			4	17	21	.12		.03			
380.0	385.0	74230	5.0	.0	2C0	3.58	.14	.02	.05	10.90			2	19	21	.09		.04			
385.0	389.0	74231	4.0	.0	2C0	3.59	.59	.04	.07	16.70			2	21	23	.05		.02			
389.0	393.5	74232	4.5	.0	2C0	3.52	.44	.12	.18	23.70			2	22	25	.08		.04			
393.5	395.5	74233	2.0	.0	2D0	4.55	.19	3.46	5.64	57.00			3	22	26	.33		.10			
395.5	399.5	74234	4.0	.0	2G4	4.68	.16	5.93	5.45	78.80			6	21	28	10.69		.18			
399.5	403.0	74235	3.5	.0	2G4	4.37	.27	5.44	5.17	75.30			10	19	29	10.51		.20			
403.0	404.5	74236	1.5	.0	2H4	4.36	.59	3.36	3.11	62.20			18	17	36	.83		.18			
404.5	405.8	74237	1.3	.0	2G4	4.63	.11	7.78	6.43	105.00			3	23	27	12.60		.16			
405.8	409.7	74238	3.9	.0	2H4	4.14	.45	4.56	4.21	77.70			29	8	38	4.32		.19			
409.7	411.0	74239	1.3	.0	2D4	3.31	.25	9.51	7.04	116.80			7	6	13	.52		.16			
436.0	440.0	74241	4.0	.0	2D4	3.47	.13	5.97	7.65	83.60			11	9	21	.25		.17			
440.0	444.0	74242	4.0	.0	2B4	3.17	.06	7.81	6.51	110.10		.07	6	6	13	.20		.15			
444.0	447.0	74243	3.0	.0	2B4	3.02	.07	6.07	5.41	94.30		.01	5	4	10	.92		.14			
447.0	450.0	74244	3.0	.0	2B0	2.79	.02	1.15	1.87	22.10		.01	3	2	6	2.07		.08			
450.0	453.0	74245	3.0	.0	2D0	3.62	.20	3.84	6.08	66.80		.07	11	13	24	1.21		.12			
453.0	457.0	74246	4.0	.0	2D4	3.90	.25	3.91	7.61	65.30		.07	13	18	32	.53		.11			
457.0	459.0	74247	2.0	.0	2B0	3.14	.16	2.61	2.93	30.40		.07	7	9	16	1.31		.08			
459.0	462.0	74248	3.0	.0	2B0	2.96	.06	1.93	2.54	21.40		.03	4	5	9	.88		.06			
462.0	465.0	74249	3.0	.0	2B0	3.22	.07	2.85	5.01	39.50		.01	7	7	15	1.63		.09			
465.0	470.0	74250	5.0	.0	2D0	3.87	.32	2.43	3.12	43.90		.01	15	19	35	.38		.11			
470.0	474.0	74251	4.0	.0	2E14	4.60	.37	2.23	3.05	40.20		.01	15	25	40	.10		.12			
474.0	477.0	74252	3.0	.0	2E14	4.18	.13	3.76	5.54	49.10		.01	9	26	36	.38		.10			
477.0	482.6	74253	5.6	.0	2E4	4.75	.12	3.45	5.29	46.00		.07	5	32	38	.09		.06			
482.6	485.0	74254	2.4	.0	2H4	4.32	.16	4.91	10.00	78.60		.01	19	14	34	.07		.09			
485.0	487.0	74255	2.0	.0	2D0	3.09	.07	1.70	2.70	18.60		.01	9	7	16	.39		.09			
487.0	491.0	74256	4.0	.0	2H4	4.23	.23	4.49	7.53	50.10		.01	13	23	37	.04		.09			
491.0	496.4	74257	5.4	.0	2F4	4.63	.04	4.86	9.38	35.20			5	32	37	.03		.07			
496.4	501.4	74258	5.0	.0	2F4	4.76	.05	6.08	10.26	42.20		.01	4	32	37	.02		.06			
501.4	505.8	74259	4.4	.0	2F0	4.67	.08	3.14	6.49	23.90		.01	5	35	41	.03		.05			
505.8	510.5	74260	4.7	.0	2H4	4.37	.20	4.00	8.78	30.80		.07	8	28	37	.03		.10			
510.5	515.5	74261	5.0	.0	2D0	3.19	.09	2.62	6.94	32.40		.07	7	6	13	.24		.10			
515.5	520.5	74262	5.0	.0	2D0	3.03	.08	1.70	4.17	27.70		.07	4	3	8	.36		.05			
520.5	525.5	74263	5.0	.0	2D0	3.18	.08	1.24	4.73	25.10		.01	6	5	12	.38		.07			
525.5	531.0	74264	5.5	.0	2D0	3.04	.07	.90	3.80	22.80		.07	5	5	11	.31		.05			
531.0	536.7	74265	5.7	.0	2D0	3.14	.05	2.35	4.86	38.10		.07	5	3	8	.30		.04			

DDH: 77-14 UTM-N: 7978.7 UTM-E: 15357.8 UTM-ELEV: 4023.4 TOTAL DEPTH: 323.0 SECTION: 129
RFE: S2 RFE DIR: 240 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %
293.0	298.0	74268	5.0	.0	2C0	3.24	.20	.45	1.21	9.70			6	13	19	.37		.06		
298.0	302.0	74269	4.0	.0	****	3.42	.05	.10	.05	4.40			2	2	4	.15		.02		
302.0	307.0	74270	5.0	.0	2AC	3.10	.21	.05	.16	10.10			1	8	10	.21		.02		
307.0	310.5	74271	3.5	.0	2AC	3.34	.21	.10	.49	13.40			1	12	13	.18		.01		
310.5	314.0	74272	3.5	.0	2AC	3.80	.04	.72	2.78	8.50		.14	1	23	24	.11		.02		
314.0	318.5	74273	4.5	.0	2F0	4.00	.24	4.71	9.32	75.60		.14	7	16	24	2.31		.16		

DDH: 77-15 UTM-N: 7794.9 UTM-E: 14799.4 UTM-ELEV: 4016.0 TOTAL DEPTH: 565.0 SECTION: 127
RFE: S2 RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
400.0	405.0	74278	5.0	.0	2C0	3.14	.29	.92	2.03	14.00		.34	6	10	16	.12		.04			
405.0	410.0	74279	5.0	.0	2A4	3.51	.13	1.81	5.79	17.50		.48	4	16	20	.12		.03			
410.0	416.0	74280	6.0	.0	2A4	3.34	.11	1.83	6.93	17.90		.27	3	15	19	.50		.04			
416.0	420.6	74281	4.6	.0	2D4	4.45	.25	5.74	6.59	57.20		.07	9	17	27	9.09		.31			
420.6	424.4	74282	3.8	.0	2B0	2.90	.12	1.50	.42	9.00		.01	3	2	5	9.95		.05			
424.4	427.9	74283	3.5	.0	2D0	3.22	.18	1.46	2.86	26.10		.01	5	7	13	9.06		.15			
427.9	431.2	74284	3.3	.0	2D4	3.52	.19	4.59	5.73	34.90		.01	10	8	18	6.58		.24			
431.2	436.2	74285	5.0	.0	2H14	4.29	.28	5.26	6.23	69.90		.07	18	16	35	4.81		.23			
436.2	441.0	74286	4.8	.0	2H14	4.16	.24	4.29	6.50	60.80		.07	18	14	33	1.39		.13			
441.0	446.0	74287	5.0	.0	2B0	3.01	.12	.90	2.43	14.10		.01	5	4	10	.76		.05			
446.0	450.0	74288	4.0	.0	2B4	3.05	.12	1.44	3.95	23.30		.01	4	5	9	.45		.04			
450.0	454.0	74289	4.0	.0	2B0	2.95	.08	1.05	2.52	21.10		.01	4	5	10	.72		.04			
454.0	458.0	74290	4.0	.0	2B0	2.94	.09	.69	1.99	16.20		.07	4	2	7	.64		.05			
458.0	463.0	74291	5.0	.0	2E4	4.63	.31	3.03	4.58	48.80		.07	12	28	41	.04		.10			
463.0	468.0	74292	5.0	.0	2E4	4.63	.35	3.23	5.31	50.30		.01	13	27	40	.03		.09			
468.0	471.0	74293	3.0	.0	2E4	4.21	.48	5.73	9.90	54.80		.14	16	18	34	.09		.12			

DDH: 77-16 UTM-N: 7986.5 UTM-E: 14589.4 UTM-ELEV: 4007.0 TOTAL DEPTH: 670.0 SECTION: 125
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----						-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
430.0	433.5	74299	3.5	.0 2A0	2.60	.01		.20	.10			3	1	4	.25		.08			
433.5	437.0	74300	3.5	.0 2B2	2.68	.07	.11	.35	3.00			3	5	8	.87		.03			
437.0	439.5	74301	2.5	.0 1D4	2.97	.17	.13	.27	4.50			8	12	20	.54		.04			
439.5	445.0	74302	5.5	.0 2A0	2.75	.13	.23	.43	5.30			6	7	14	.21		.04			
445.0	450.0	74303	5.0	.0 2C0	2.88	.40	1.08	2.82	13.80		.07	6	8	14	.28		.07			
450.0	455.0	74304	5.0	.0 2FG4	4.56	.22	5.73	7.21	76.60		.07	8	24	32	6.76		.22			
455.0	460.0	74305	5.0	.0 2FG4	4.59	.13	5.29	6.44	65.10		1.30	5	30	36	2.29		.17			
460.0	463.5	74306	3.5	.0 2DG7	3.51	.26	3.71	4.97	53.60		.01	14	7	21	6.69		.12			
463.5	467.0	74307	3.5	.0 2DG7	3.36	.26	2.36	4.23	35.00		.27	6	9	15	10.99		.14			
467.0	472.0	74308	5.0	.0 2G4	4.77	.20	5.87	6.22	82.50		.34	6	26	33	5.13		.21			
472.0	477.0	74309	5.0	.0 2G0	4.51	.27	4.40	4.90	65.20		.48	6	23	29	15.41		.32			
477.0	482.0	74310	5.0	.0 2G4	4.55	.19	5.76	6.59	82.40		.62	5	21	26	17.67		.29			
482.0	487.0	74311	5.0	.0 2G4	4.67	.22	5.44	6.98	80.70		.07	6	19	26	20.15		.28			
487.0	492.0	74312	5.0	.0 2G4	4.56	.22	5.60	5.94	90.10		.34	7	22	29	13.42		.31			
492.0	497.5	74313	5.5	.0 2G4	4.60	.26	5.89	6.44	85.10		.07	12	24	36	2.69		.19			
497.5	501.5	74314	4.0	.0 2H4	4.31	.22	6.81	8.35	99.70		.14	15	18	33	1.55		.14			
501.5	506.5	74315	5.0	.0 2D0	3.01	.15	2.00	4.55	32.90		.01	8	5	14	.20		.05			
506.5	510.0	74316	3.5	.0 2C0	2.84	.14	.90	3.06	14.40		.01	6	4	10	.22		.03			
510.0	514.5	74317	4.5	.0 2D0	3.03	2.00	.44	5.43	69.90		1.30	13	4	18	.23		.06			
514.5	519.0	74318	4.5	.0 2A0	2.67	.27	.37	1.50	13.90		.07	5	1	6	.40		.06			
519.0	522.0	74319	3.0	.0 2A0	2.61	.12	.05	.19	3.90		.01	5		6	.67		.08			

DDH: 77018 UTM-N: 9790.4 UTM-E: 14417.4 UTM-ELEV: 3831.1 TOTAL DEPTH: 297.0 SECTION:
 RFE: RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	ASSAYS														S.G. W.R.
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Pt %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	
26.0	31.0	74365	5.0	.0	****	4.65	.11	1.52	3.70	9.20			5	28	33	.04		.11			
31.0	36.0	74366	5.0	.0	****	4.18	.25	.14	1.79	6.30			4	32	37	.01		.08			
36.0	40.0	74367	4.0	.0	****	3.77	.17	.12	1.05	5.10			3	28	31	.02		.06			
40.0	43.0	74368	3.0	.0	****	3.95	.17	.61	1.03	6.20			3	30	33	.01		.07			
43.0	47.0	74369	4.0	.0	****	4.12	.16	.13	1.88	5.80			4	29	33	.02		.09			
47.0	50.0	74370	3.0	.0	****	3.59	.13	1.50	7.13	7.40			3	23	26	.03		.05			
50.0	53.5	74371	3.5	.0	****	4.00	.08	4.68	10.51	15.80			3	23	26	.02		.04			
53.5	56.0	74372	2.5	.0	****	3.76	.14	1.27	4.10	6.50			3	23	26	.01		.07			
56.0	59.0	74373	3.0	.0	****	4.38	.14	.17	3.36	4.20			5	31	37	.01		.14			
59.0	62.0	74374	3.0	.0	****	4.25	.14	.29	2.15	6.20			6	33	39	.02		.15			
62.0	66.0	74375	4.0	.0	****	4.19	.04	.63	2.60	4.90			2	33	36	.03		.06			
66.0	69.0	74376	3.0	.0	****	4.17	.05	.86	3.68	5.40			2	32	34	.03		.04			
69.0	70.5	74377	1.5	.0	****	3.71	.05	3.77	12.37	13.40			3	18	21	.09		.03			
70.5	71.5	74378	1.0	.0	****	3.14	.04	1.25	3.30	6.20			1	17	19	.03		.02			
71.5	76.5	74379	5.0	.0	****	3.48	.04	7.73	20.00	28.00			4	11	16	.11		.02			
76.5	81.5	74380	5.0	.0	****	3.88	.04	.54	.50	4.50			1	25	26	.03		.01			
81.5	86.5	74381	5.0	.0	****	3.59	.03	.20	.31	4.20			1	25	27	.02		.02			
86.5	91.0	74382	4.5	.0	****	3.71	.03	5.22	9.89	22.50			2	18	21	.10		.02			
91.0	96.0	74383	5.0	.0	****	3.33	.04	1.37	7.43	11.80			3	17	20	.11		.03			
96.0	101.0	74384	5.0	.0	****	3.41	.03	3.98	10.11	18.20			2	16	19	.11		.02			
101.0	106.0	74385	5.0	.0	****	3.66	.03	4.29	9.36	20.00			3	18	21	.09		.03			
106.0	113.0	74386	7.0	.0	****	3.43	.04	1.76	7.25	13.60			3	16	19	.13		.03			
113.0	118.0	74387	5.0	.0	****	3.25	.04	1.94	4.73	16.10			2	14	17	.19		.02			
118.0	123.0	74388	5.0	.0	****	3.20	.02	.50	1.03	6.20			2	15	17	.22		.02			
123.0	128.0	74389	5.0	.0	****	3.56	.03	.90	4.14	8.90			2	24	26	.07		.01			
128.0	132.0	74390	4.0	.0	****	4.73	.02	2.08	6.75	12.80			2	38	41	.02		.02			
132.0	137.0	74391	5.0	.0	****	4.41	.03	7.66	16.60	45.10			3	26	29	.02		.02			
137.0	141.0	74392	4.0	.0	****	4.24	.05	9.37	22.80	50.60			4	18	23	.02		.03			
141.0	145.0	74393	4.0	.0	****	3.25	.03	.83	1.95	11.90			2	16	19	.18		.03			
145.0	149.0	74394	4.0	.0	****	3.40	.03	.23	.82	5.20			3	18	21	.17		.02			
149.0	153.0	74395	4.0	.0	****	3.55	.11	.65	3.21	8.90			5	22	28	.18		.04			
153.0	157.0	74396	4.0	.0	****	3.36	.06	2.76	6.89	24.10			3	15	19	.16		.03			
157.0	161.0	74397	4.0	.0	****	3.37	.04	3.69	14.70	32.70			3	12	16	.13		.03			
161.0	165.0	74398	4.0	.0	****	3.25	.03	2.43	9.00	24.10			2	14	16	.12		.02			
165.0	169.0	74399	4.0	.0	****	3.43	.03	2.22	8.27	19.80			3	18	21	.11		.02			
169.0	174.0	74400	5.0	.0	****	4.54	.02	1.38	3.60	9.70			1	41	42	.02		.02			
174.0	179.0	74401	5.0	.0	****	4.73	.02	1.38	2.48	10.70			2	42	44	.02		.02			
179.0	184.0	74402	5.0	.0	****	3.11	.11	2.85	10.61	26.80			7	6	13	.18		.04			
184.0	187.0	74403	3.0	.0	****	4.69	.04	.54	1.50	6.60			1	44	45	.01		.02			
187.0	192.0	74404	5.0	.0	****	3.37	.04	3.37	9.91	23.10			3	16	20	.10		.02			
192.0	195.0	74405	3.0	.0	****	4.29	.02	2.18	4.11	13.60			2	36	38	.02		.02			
195.0	200.0	74406	5.0	.0	****	4.49	.02	1.72	3.50	8.90			1	39	41	.03		.03			
200.0	205.0	74407	5.0	.0	****	4.08	.03	2.14	5.21	14.80			2	32	34	.05		.02			
205.0	210.0	74408	5.0	.0	****	4.27	.02	3.26	6.75	19.20			2	35	37	.02		.03			
210.0	214.0	74409	4.0	.0	****	3.73	.04	2.49	9.23	20.00			3	22	25	.02		.04			
214.0	219.0	74410	5.0	.0	****	3.47	.05	2.67	8.77	17.90			4	16	20	.09		.04			
219.0	224.0	74411	5.0	.0	****	3.26	.11	2.90	4.85	28.00			2	17	19	.09		.03			
224.0	229.0	74412	5.0	.0	****	3.22	.11	.32	2.40	7.50			2	14	16	.11		.02			
229.0	234.0	74413	5.0	.0	****	3.19	.21	.62	5.38	17.00			5	8	14	.10		.04			
234.0	239.0	74414	5.0	.0	****	3.32	.17	3.02	10.51	22.70			6	10	17	.15		.04			
239.0	243.0	74415	4.0	.0	****	3.44	.06	3.71	9.45	25.60			3	13	17	.18		.01			

DDH: 77018 UTM-N: 9790.4 UTM-E: 14417.4 UTM-ELEV: 3831.1 TOTAL DEPTH: 297.0 SECTION:
RFE: RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

---DEPTHS---						-----ASSAYS-----																	
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.		
243.0	247.0	74416	4.0	.0	****	3.51	.05	4.13	11.48	38.30			4	14	19	.14		.02					
247.0	252.0	74417	5.0	.0	****	4.87	.02	1.34	2.38	14.30			1	39	40	.01		.01					
252.0	257.0	74418	5.0	.0	****	3.28	.20	.88	3.76	14.20			9	12	21	.15		.04					
257.0	262.0	74419	5.0	.0	****	3.34	.13	.34	2.64	8.60			9	14	23	.14		.02					
262.0	267.0	74420	5.0	.0	****	3.39	.10	3.11	3.33	43.90			7	14	21	.15		.03					
267.0	272.0	74421	5.0	.0	****	3.33	.11	2.16	5.77	29.50			5	9	15	.22		.04					
272.0	277.0	74422	5.0	.0	****	3.48	.13	.92	6.69	17.10			6	13	20	.13		.06					
277.0	282.0	74423	5.0	.0	****	3.53	.09	1.24	4.81	18.60			4	19	23	.14		.03					
282.0	287.0	74424	5.0	.0	****	3.68	.24	1.28	2.98	17.10			8	18	26	.12		.04					
287.0	292.0	74425	5.0	.0	****	4.28	.43	4.77	3.74	33.80			11	24	35	.04		.07					
292.0	297.0	74426	5.0	.0	****	3.47	.14	1.90	3.33	24.50			5	19	25	.13		.02					

[illegible]

DDH: 77021 UTM-N: 9957.9 UTM-E: 14355.8 UTM-ELEV: 3853.0 TOTAL DEPTH: 80.0 SECTION:
RFE: RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----															
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.	
9.5	13.0	74446	3.5	.0	****	3.26	.04	.92	2.70	9.50		6	14	21	.13		.15					
13.0	16.0	74447	3.0	.0	****	3.48	.02	.84	3.55	8.40		2	25	27	.14		.03					
16.0	21.0	74448	5.0	.0	****	3.77	.03	1.27	4.77	9.50		2	29	31	.11		.02					
21.0	26.0	74449	5.0	.0	2C0	3.25	.06	2.79	4.97	28.60		3	10	14	.20		.02					
26.0	31.0	74450	5.0	.0	****	3.20	.09	2.36	3.50	21.10		4	13	18	.20		.04					
31.0	36.0	74451	5.0	.0	****	3.21	.05	3.43	3.85	31.80		3	10	14	.20		.04					
36.0	41.0	74452	5.0	.0	****	2.98	.07	1.89	4.77	18.80		3	6	10	.27		.02					
41.0	43.5	74453	2.5	.0	****	3.49	.07	1.77	3.73	19.50		4	22	27	.22		.05					
43.5	47.5	74454	4.0	.0	****	4.31	.02	4.98	14.16	34.90		4	22	26	.02		.03					
47.5	50.5	74455	3.0	.0	****	3.05	.07	6.87	15.92	50.20		4	23	28	.02		.04					
50.5	53.5	74456	3.0	.0	****	3.23	.30	1.30	2.90	13.30		6	12	19	.21		.02					
53.5	57.0	74457	3.5	.0	****	3.41	.13	5.06	10.24	51.20		5	14	19	.06		.02					

DDH: 78005 UTM-N: 9282.6 UTM-E: 13918.3 UTM-ELEV: 3748.1 TOTAL DEPTH: 173.0 SECTION:
 RFE: RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	ASSAYS														
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
18.1	20.6	74482	2.5	.0	****	2.97	.35	.76	1.05	10.30			7	8	16	.10		.09			
20.6	23.1	74483	2.5	.0	****	2.97	.06	1.80	4.49	10.30			1	5	6	.10		.02			
23.1	25.6	74484	2.5	.0	****	2.97	.04	1.53	2.70	10.30			1	3	4	.10		.02			
25.6	28.1	74485	2.5	.0	****	2.97	.04	1.39	2.71	10.30				4	4	.10		.02			
28.1	30.6	74486	2.5	.0	****	2.97	.03	1.20	1.98	10.30			1	5	7	.10		.03			
30.6	33.1	74487	2.5	.0	****	2.97	.05	1.93	3.32	10.30			6	3	9	.10		.09			
33.1	35.6	74488	2.5	.0	****	2.97	.20	3.11	3.98	10.30			10	11	21	.10		.16			
35.6	38.1	74489	2.5	.0	****	2.97	.29	3.06	.71	10.30			24	3	28	.10		.37			
38.1	40.6	74490	2.5	.0	****	4.42	.41	3.34	4.11	61.70			17	16	33	1.59		.35			
40.6	43.1	74491	2.5	.0	****	4.42	.36	3.98	5.32	61.70			19	17	36	1.59		.42			
43.1	45.6	74492	2.5	.0	****	4.42	.40	6.24	8.95	61.70			11	22	34	1.59		.30			
45.6	48.1	74493	2.5	.0	****	4.42	.29	5.84	8.97	61.70			14	18	33	1.59		.41			
48.1	50.6	74494	2.5	.0	****	4.42	.13	4.24	5.95	61.70			9	25	35	1.59		.39			
50.6	53.1	74495	2.5	.0	****	4.42	.34	4.55	6.52	61.70			14	17	32	1.59		.52			
53.1	55.6	74496	2.5	.0	****	4.42	.30	4.12	5.24	61.70			10	25	36	1.59		.40			
55.6	58.1	74497	2.5	.0	****	4.42	.25	5.86	7.60	61.70			10	26	36	1.59		.35			
58.1	60.6	74498	2.5	.0	****	4.65	.09	7.71	7.14	65.10			4	31	36	.93		.29			
60.6	63.1	74499	2.5	.0	****	4.65	.14	7.31	8.68	65.10			3	28	32	.93		.24			
63.1	65.6	74500	2.5	.0	****	4.65	.11	5.38	7.99	65.10			3	27	31	.93		.18			
65.6	68.1	74501	2.5	.0	****	4.65	.12	7.01	10.78	65.10			3	27	30	.93		.10			
68.1	70.6	74502	2.5	.0	****	4.65	.09	7.94	10.65	65.10			2	27	30	.93		.08			
70.6	73.1	74503	2.5	.0	****	4.65	.22	6.26	10.35	65.10			3	28	31	.93		.13			
73.1	75.6	74504	2.5	.0	****	4.65	.23	6.50	7.98	65.10			4	29	33	.93		.33			
75.6	78.1	74505	2.5	.0	****	4.65	.20	7.18	8.61	65.10			3	29	33	.93		.21			
78.1	80.6	74506	2.5	.0	****	4.61	.16	5.66	8.22	61.70			3	33	36	.68		.29			
80.6	83.1	74507	2.5	.0	****	4.61	.18	6.31	8.09	61.70			3	27	30	.68		.16			
83.1	85.6	74508	2.5	.0	****	4.61	.19	5.42	7.91	61.70			5	27	32	.68		.24			
85.6	88.1	74509	2.5	.0	****	4.61	.49	5.89	7.21	61.70			4	29	34	.68		.16			
88.1	90.6	74510	2.5	.0	****	4.61	.45	23.50	8.52	61.70			23	14	38	.68		.34			
90.6	93.1	74511	2.5	.0	****	4.61	.25	9.80	10.12	61.70			5	27	32	.68		.36			
93.1	95.6	74512	2.5	.0	****	4.61	.32	6.06	6.44	61.70			6	30	37	.68		.41			
95.6	98.1	74513	2.5	.0	****	4.61	.14	5.45	5.88	61.70			5	32	37	.68		.29			
98.1	100.6	74514	2.5	.0	****	4.05	.15	4.20	4.76	72.00			5	31	36	1.02		.28			
100.6	103.1	74515	2.5	.0	****	4.05	.21	7.33	7.66	72.00			4	28	33	1.02		.21			
103.1	105.6	74516	2.5	.0	****	4.05	.31	4.94	6.28	72.00			5	30	36	1.02		.29			
105.6	108.1	74517	2.5	.0	****	4.05	.28	4.96	7.50	72.00			6	25	31	1.02		.11			
108.1	110.6	74518	2.5	.0	****	4.05	.27	4.06	10.21	72.00			18	7	25	1.02		.11			
110.6	113.1	74519	2.5	.0	****	4.05	.12	1.88	6.98	72.00			5	5	10	1.02		.07			
113.1	115.6	74520	2.5	.0	****	4.05	.05	3.08	4.13	72.00			3	3	6	1.02		.05			
115.6	118.1	74521	2.5	.0	****	4.05	.07	9.00	5.35	72.00			2	4	7	1.02		.04			
118.1	120.6	74522	2.5	.0	****	3.91	.05	1.63	1.80	44.60			2	2	5	.03		.05			
120.6	123.1	74523	2.5	.0	****	3.91	.03	6.62	3.41	44.60			2	1	3	.03		.05			
123.1	125.6	74524	2.5	.0	****	3.91	.01	2.39	2.01	44.60			1		1	.03		.03			
125.6	128.1	74525	2.5	.0	****	3.91	.03	2.72	4.33	44.60			2	1	3	.03		.04			
128.1	130.6	74526	2.5	.0	****	3.91	.34	2.63	5.06	44.60			8	20	29	.03		.09			
130.6	133.1	74527	2.5	.0	****	3.91	.26	5.73	8.49	44.60			33	8	42	.03		.13			
133.1	135.6	74528	2.5	.0	****	3.91	.55	2.76	2.64	44.60			50	2	52	.03		.05			
135.6	138.1	74529	2.5	.0	****	3.91	.52	3.26	3.10	44.60			50	1	52	.03		.04			
138.1	140.6	74530	2.5	.0	****	3.33	.48	3.66	4.12	17.10			39	3	42	.06		.04			
140.6	143.1	74531	2.5	.0	****	3.33	.55	4.23	8.29	17.10			44	2	46	.06		.06			
143.1	145.6	74532	2.5	.0	****	3.33	.29	3.33	13.01	17.10			13	3	17	.06		.21			

DDH: 78005 UTM-N: 9282.6 UTM-E: 13918.3 UTM-ELEV: 3748.1 TOTAL DEPTH: 173.0 SECTION:
RFE: RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
145.6	148.1	74533	2.5	.0	****	3.33	.06	1.63	7.08	17.10			3	3	6	.06		.12			
148.1	150.6	74534	2.5	.0	****	3.33	.06	.16	.70	17.10			2	3	5	.06		.04			
150.6	153.1	74535	2.5	.0	****	3.33	.05	.03	.06	17.10			2	3	6	.06		.04			
153.1	155.6	74536	2.5	.0	****	3.33	.02	.07	.08	17.10			2	3	5	.06		.04			
155.6	158.1	74537	2.5	.0	****	3.33	.02	.03	.07	17.10			2	2	4	.06		.04			
158.1	160.6	74538	2.5	.0	****	2.79	.08	2.84	4.38	30.90			4	2	7	.10		.09			
160.6	163.1	74539	2.5	.0	****	2.79	.07	2.80	4.64	30.90			3	4	8	.10		.08			
163.1	165.6	74540	2.5	.0	****	2.79	.09	1.68	3.93	30.90			2	3	6	.10		.02			
165.6	168.1	74541	2.5	.0	****	2.79	.09	1.26	2.09	30.90			1	2	3	.10		.01			
168.1	170.6	74542	2.5	.0	****	2.79	.05	1.72	3.88	30.90			1	2	4	.10		.03			
170.6	173.1	74543	2.5	.0	****	2.79	.08	.62	1.06	30.90			2	1	4	.10		.06			

DDH: 78006 UTM-N: 9482.1 UTM-E: 13915.9 UTM-ELEV: 3709.1 TOTAL DEPTH: 59.1 SECTION:
RFE: RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %
5.0	8.0	74546	3.0	.0	****	5.18	.37	5.20	5.04	65.10			3	24	28	24.00		.27		
8.0	10.5	74547	2.5	.0	****	5.18	.17	6.93	7.42	65.10			3	16	20	24.00		.37		
10.5	13.0	74548	2.5	.0	****	5.18	.10	5.66	7.13	65.10			2	12	15	24.00		.25		
13.0	16.0	74549	3.0	.0	****	5.18	.29	1.67	1.41	65.10			1	37	38	24.00		.06		
16.0	19.1	74550	3.1	.0	****	5.18	.23	4.04	3.62	65.10			2	33	36	24.00		.13		
19.1	23.2	74551	4.1	.0	****	4.39	.17	1.01	.49	17.10				30	31	.03		.02		
23.2	27.6	74552	4.4	.0	****	4.39	.60	2.22	3.42	17.10			2	37	40	.03		.09		
27.6	29.1	74553	1.5	.0	****	4.39	.37	5.26	7.53	17.10			20	18	39	.03		.09		
29.1	31.6	74554	2.5	.0	****	4.39	.43	3.48	5.32	17.10			5	33	38	.03		.06		
31.6	34.1	74555	2.5	.0	****	4.39	.24	3.06	4.70	17.10			3	34	37	.03		.11		
34.1	36.6	74556	2.5	.0	****	4.39	.32	2.63	4.77	17.10			2	36	38	.03		.07		
36.6	39.1	74557	2.5	.0	****	4.39	.62	4.49	7.09	17.10			20	19	39	.03		.05		
39.1	41.6	74558	2.5	.0	****	3.03	.20	1.45	3.18	27.40			3	3	7	.10		.04		
41.6	44.1	74559	2.5	.0	****	3.03	.14	1.43	3.05	27.40			2	2	5	.10		.03		
44.1	46.6	74560	2.5	.0	****	3.03	.26	2.75	3.80	27.40			5	6	11	.10		.03		
46.6	49.1	74561	2.5	.0	****	3.03	.61	2.17	4.85	27.40			17	7	24	.10		.04		
49.1	51.6	74562	2.5	.0	****	3.03	.25	.77	2.24	27.40			3	5	9	.10		.03		
51.6	54.1	74563	2.5	.0	****	3.03	.23	2.68	6.00	27.40			4	3	8	.10		.09		
54.1	56.6	74564	2.5	.0	****	3.03	.13	2.17	2.62	27.40			1	1	2	.10		.04		
56.6	59.1	74565	2.5	.0	****	3.03	.21	.82	.55	27.40			3	3	7	.10		.03		

DDH: 78023 UTM-N: 9496.6 UTM-E: 14311.1 UTM-ELEV: 3712.6 TOTAL DEPTH: 123.0 SECTION:
RFE: RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
3.0	23.0	74575	20.0	.0	****	4.51	.31	3.39	2.80	26.70			3	29	32	3.07		.12			
23.0	43.0	74576	20.0	.0	****	4.48	.30	2.01	3.60	25.60			4	25	30	.19		.14			
43.0	63.0	74577	20.0	.0	****	4.85	.35	3.05	5.19	13.10			1	33	35	.19		.03			
63.0	83.0	74578	20.0	.0	****	4.64	.33	2.10	4.26	9.60			2	30	33	.20		.07			
83.0	103.0	74579	20.0	.0	****	4.72	.25	2.92	4.74	17.40			5	4	10	.19		.04			
103.0	123.0	74580	20.0	.0	****	4.15	.19	3.78	5.84	28.00			4	8	13	.26		.07			

DDH: 78024 UTM-N: 9684.9 UTM-E: 14494.2 UTM-ELEV: 3723.1 TOTAL DEPTH: 163.0 SECTION:
RFE: RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

---DEPTHS---						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
13.0	33.0	74583	20.0	.0	****	4.14	.07	3.85	7.49	12.10			1	28	30	.21		.03			
33.0	53.0	74584	20.0	.0	****	4.20	.07	3.96	7.34	17.10			3	20	23	.19		.05			
53.0	73.0	74585	20.0	.0	****	3.29	.07	.90	1.90	24.30			2	29	31	.31		.01			
73.0	93.0	74586	20.0	.0	****	3.40	.11	.92	1.35	9.30			2	36	39	.27		.03			
93.0	113.0	74587	20.0	.0	****	4.36	.08	2.46	3.82	38.20			1	36	37	.18		.01			
113.0	133.0	74588	20.0	.0	****	4.44	.07	1.38	2.31	12.40			1	5	6	.19		.02			
133.0	153.0	74589	20.0	.0	****	2.72	.11	1.19	1.64	15.60			1	10	12	.37		.03			
153.0	163.0	74590	10.0	.0	****	2.93	.15	1.42	2.52	13.70			3	36	39	.34		.02			

DDH: 78025 UTM-N: 9508.9 UTM-E: 14078.6 UTM-ELEV: 3696.3 TOTAL DEPTH: 86.0 SECTION:
RFE: RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----						-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
11.0	26.0	74593	15.0	.0	****	4.73	.50	3.23	4.82	21.10		1	20	22	.20		.05			
26.0	46.0	74594	20.0	.0	****	3.61	.30	3.08	5.81	29.90		3	35	39	.27		.02			
46.0	66.0	74595	20.0	.0	****	3.34	.31	11.00	2.16	120.00		6	2	8	.24		.06			
66.0	86.0	74596	20.0	.0	****	2.78	.33	.29	.54	19.30		5	15	20	.30		.06			

DDH: 78026 UTM-N: 9700.0 UTM-E: 14100.0 UTM-ELEV: 3711.0 TOTAL DEPTH: 121.0 SECTION:
RFE: RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
10.0	21.0	74599	11.0	.0	****	4.63	.48	1.79	3.86	8.40			6	33	40	.19		.18			
21.0	41.0	74600	20.0	.0	****	4.40	.36	.58	1.93	21.80			7	29	37	.19		.19			
41.0	61.0	74601	20.0	.0	****	4.60	.52	1.18	2.92	19.60			4	33	38	.19		.10			
61.0	81.0	74602	20.0	.0	****	4.36	.31	4.04	6.56	10.30			2	36	38	.20		.05			
81.0	101.0	74603	20.0	.0	****	4.20	.06	4.10	8.94	4.70			1	38	39	.21		.02			
101.0	121.0	74604	20.0	.0	****	3.62	.16	1.70	3.97	16.20			3	3	6	.23		.02			

DDH: 78027 UTM-N: 9579.2 UTM-E: 13824.2 UTM-ELEV: 3691.3 TOTAL DEPTH: 31.0 SECTION:
RFE: RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %
6.0	21.0	74607	15.0	.0	****	3.01	.15	2.03	3.56	23.30			3	3	7	.27		.04		
21.0	31.0	74608	10.0	.0	****	2.61	.20	1.95	3.55	17.70			5	16	21	.26		.01		

DDH: 79-03 UTM-N: 9491.5 UTM-E: 14715.2 UTM-ELEV: 3879.6 TOTAL DEPTH: 516.0 SECTION: 118+000
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	ASSAYS														
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
139.2	140.0	74616	.8	.0	2D09	3.40	.30	2.55	1.69	41.80		.44	10	7	17	.80		.30			
140.0	145.0	74617	5.0	.0	2E46	4.57	.24	6.89	6.43	120.00		.31	16	10	27	1.70		.43			
145.0	150.0	74618	5.0	.0	2E46	4.55	.16	6.76	5.96	111.50		.45	5	18	23	2.00		.38			
150.0	155.0	74619	5.0	.0	2E46	4.68	.11	7.49	7.67	100.50		.72	4	16	20	2.60		.28			
155.0	160.0	74620	5.0	.0	2E46	4.72	.17	7.46	6.41	112.20		.84	8	15	24	2.30		.39			
160.0	165.0	74621	5.0	.0	2E46	4.74	.15	6.39	5.56	90.50		.61	7	18	26	2.00		.46			
165.0	170.0	74622	5.0	.0	2E46	4.58	.13	7.15	5.98	104.10		.64	6	14	20	2.50		.44			
170.0	175.0	74623	5.0	.0	2E46	4.60	.09	3.74	3.90	57.60		.53	3	25	29	1.80		.18			
175.0	180.0	74624	5.0	.0	2G40	4.67	.08	4.70	5.83	34.30		.78	2	22	25	2.10		.12			
180.0	185.0	74625	5.0	.0	2E4	4.78	.02	3.51	5.72	46.70		.23	2	32	34	1.20		.02			
185.0	188.5	74626	3.5	.0	2D4	4.01	.09	3.47	10.30	52.50		.36	3	18	22	1.10		.04			
227.5	230.0	74628	2.5	.0	2D0	4.08	.15	3.36	3.63	29.20		.14	2	28	31			.02			
230.0	235.0	74629	5.0	.0	2D09	4.09	.13	.69	.46	8.60		.09	1	33	34			.01			
235.0	240.0	74630	5.0	.0	2F00	4.43	.24	2.15	3.46	20.60		.08	1	35	37			.01			
240.0	245.0	74631	5.0	.0	2C3	4.54	.27	1.19	1.49	11.00		.06	2	38	41			.10			
245.0	250.0	74632	5.0	.0	2F00	4.46	.18	1.42	1.93	4.50		.05	8	34	42			.36			
250.0	255.0	74633	5.0	.0	2F4	4.61	.15	6.50	9.71	44.90		.04	7	28	35			.30			
255.0	260.0	74634	5.0	.0	2E4	4.70	.16	2.66	4.10	13.00		.03	6	35	42			.19			
260.0	265.0	74635	5.0	.0	2D40	4.36	.17	5.73	8.92	20.60		.18	5	27	32			.10			
265.0	270.0	74636	5.0	.0	2D4	3.80	.11	3.87	3.49	78.60		.93	1	24	26			.03			
270.0	275.0	74637	5.0	.0	2D4	3.78	.11	4.03	8.02	18.20		.37	3	20	23			.03			
275.0	280.0	74638	5.0	.0	2F40	4.16	.12	4.90	8.41	23.70		.38	5	24	30			.18			
280.0	285.0	74639	5.0	.0	2F40	4.08	.16	4.96	9.70	12.70		.12	7	21	28			.28			
285.0	290.0	74640	5.0	.0	2F40	4.03	.19	.36	3.38	2.10		.07	10	22	32			.29			
290.0	295.0	74641	5.0	.0	2C39	3.75	.24	.14	1.20	3.10		.09	7	21	29			.18			
295.0	300.0	74642	5.0	.0	2C39	4.01	.36	.07	1.61	2.10		.07	7	25	33			.18			
300.0	305.0	74643	5.0	.0	2C39	3.77	.62	.06	.97	4.10		.07	7	21	28			.17			
305.0	310.0	74644	5.0	.0	2E09	3.98	.41	.27	1.53	2.10		.05	9	25	35			.25			
310.0	315.0	74645	5.0	.0	2E09	4.11	.25	.13	1.36	2.10		.05	9	26	36			.26			
315.0	320.0	74646	5.0	.0	2C39	4.01	.43	.27	1.68	3.80		.05	6	28	34			.17			
320.0	325.0	74647	5.0	.0	2C39	4.30	.55	.06	.87	3.40		.04	4	34	38			.15			
325.0	330.0	74648	5.0	.0	2E1	4.39	.52	.02	.81	2.40		.05	5	35	40			.15			
330.0	335.0	74649	5.0	.0	2E1	4.27	.18	.02	1.14	1.00		.05	4	34	39			.13			
335.0	340.0	74650	5.0	.0	2E1	4.43	.11	.35	2.41	1.70		.05	4	35	39			.11			
340.0	345.0	74651	5.0	.0	2F4	4.48	.08	4.69	9.12	9.30		.05	3	29	33			.08			
345.0	350.0	74652	5.0	.0	2E4	4.31	.03	7.46	12.10	22.30		.05	2	23	26			.02			
350.0	355.0	74653	5.0	.0	2E4	4.33	.03	5.13	11.00	18.20		.05	3	25	28			.02			
355.0	360.0	74654	5.0	.0	2D0	3.57	.04	1.45	4.64	7.60		.09	3	17	21			.06			
360.0	365.0	74655	5.0	.0	2D05	3.74	.06	.95	3.10	6.90		.07	2	22	25			.02			
365.0	370.0	74656	5.0	.0	2E00	4.70	.02	2.37	4.96	13.40		.07	1	37	38			.01			
370.0	375.0	74657	5.0	.0	2E0	4.89	.01	.94	.66	6.90		.05	4	40	45			.01			
375.0	380.0	74658	5.0	.0	2E0	4.86	.01	.08	.17	.70		.05	3	42	45			.01			
380.0	385.0	74659	5.0	.0	2E0	4.86	.02	.96	1.82	6.90		.05	3	40	44			.01			
385.0	390.0	74660	5.0	.0	2C3	4.51	.05	.78	2.02	17.20		.06	3	36	40			.02			
390.0	395.0	74661	5.0	.0	2C3	3.38	.11	.48	1.65	8.90		.06	3	17	20			.01			
395.0	400.0	74662	5.0	.0	2D0	3.35	.09	2.70	4.22	50.10		.08	3	12	15			.03			
400.0	401.0	74663	1.0	.0	2D0	3.12	.09	2.95	3.26	78.20		.05	4	5	10			.04			

DDH: 80-01 UTM-N: 9136.0 UTM-E: 14402.0 UTM-ELEV: 3905.0 TOTAL DEPTH: 584.0 SECTION: 118+000
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Pt %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
371.5	374.5	74670	3.0	.0	2C35	3.51	.37	.20	.92	8.40				8 18	26	.05		.04			
374.5	377.0	74671	2.5	.0	2D5	3.17	.20	2.97	4.63	34.20				4 8	13	.03		.04			
377.0	379.5	74672	2.5	.0	2D5	3.38	.10	1.18	5.11	18.40				2 10	13	.03		.02			
379.5	382.0	74673	2.5	.0	2D45	3.36	.11	2.12	11.10	21.50				1 12	14	.05		.04			
382.0	385.0	74674	3.0	.0	2F0	4.83	.12	3.88	4.66	44.80				2 32	34	.10		.09			
385.0	387.5	74675	2.5	.0	2G48	4.63	.24	6.12	7.19	83.70				4 24	28	9.75		.26			
387.5	390.0	74676	2.5	.0	2G48	4.67	.33	5.34	5.95	76.50				5 25	31	8.07		.29			
390.0	392.5	74677	2.5	.0	2G48	4.65	.31	5.32	6.09	77.80				7 21	29	11.88		.39			
392.5	395.0	74678	2.5	.0	2G48	4.74	.25	5.71	6.92	84.00				4 21	25	18.06		.31			
395.0	397.5	74679	2.5	.0	2G48	4.63	.26	5.43	6.86	82.10				5 21	26	14.31		.34			
397.5	400.0	74680	2.5	.0	2G48	5.03	.27	5.87	6.01	83.40				5 23	29	11.00		.25			
400.0	402.5	74681	2.5	.0	2G48	4.61	.21	5.10	6.45	72.20				4 25	30	8.65		.30			
402.5	405.0	74682	2.5	.0	2G41	4.55	.14	4.39	6.25	51.30				3 27	30	8.69		.28			
405.0	407.5	74683	2.5	.0	2G41	4.83	.03	5.26	6.19	71.90				2 27	30	7.80		.19			
407.5	410.0	74684	2.5	.0	2G41	4.78	.03	4.79	6.23	67.80				2 28	31	5.79		.17			
410.0	412.5	74685	2.5	.0	2G41	4.78	.05	5.69	6.89	78.10				3 27	30	6.15		.13			
412.5	414.0	74686	1.5	.0	2H46	4.42	.37	8.27	7.16	113.50				22 9	31	3.17		.51			
414.0	416.0	74687	2.0	.0	2G48	4.59	.09	6.92	6.52	107.60				9 16	25	16.89		.52			
416.0	418.0	74688	2.0	.0	2G48	4.59	.10	5.75	5.35	86.20				9 20	29	10.41		.53			
418.0	420.5	74689	2.5	.0	2A06	2.85	.05	.52	.59	12.10				2 2	4	5.51		.06			
420.5	423.0	74690	2.5	.0	2A06	2.79	.06	.60	.79	16.20				2 2	5	3.34		.06			
423.0	425.0	80025	2.0	.0	2L14		.01	.03	.01	2.80				1 2	3	3.56		.03			
425.0	427.5	80026	2.5	.0	2L14		.05	.98	1.18	20.53				2 2	5	3.55		.11			
427.5	430.0	80027	2.5	.0	2L14		.07	1.97	2.48	42.30				3 4	7	3.91		.18			
430.0	431.5	80028	1.5	.0	2L14		.11	1.40	1.76	32.97				4 6	10	3.82		.16			
431.5	435.0	80029	3.5	.0	2L14		.04	.56	.86	19.28				4 2	6	4.28		.10			
435.0	437.5	80030	2.5	.0	2L14		.07	1.00	1.78	31.17				4 4	9	6.79		.12			
437.5	440.0	80031	2.5	.0	2A0		.13	.70	1.45	29.86				3 4	8	9.45		.09			
440.0	442.0	80032	2.0	.0	2L14		.15	3.37	3.02	87.81				6 5	12	5.53		.21			
442.0	444.0	80033	2.0	.0	2L14		.18	1.61	1.99	50.39				5 4	10	3.80		.17			
444.0	446.0	80034	2.0	.0	2D4		.18	10.90	6.87	261.26				10 8	18	4.57		.45			
446.0	448.0	80035	2.0	.0	2L14		.08	4.46	1.18	87.71				2 2	4	6.39		.10			
448.0	450.0	74692	2.0	.0	2D69	3.48	.24	2.98	3.54	75.50				5 11	16	7.24		.18			
450.0	453.0	74693	3.0	.0	2H49	4.20	.42	4.76	6.58	93.60				17 18	35	.15		.26			
453.0	457.0	74694	4.0	.0	2D9	2.96	.31	2.29	4.76	59.70				3 4	8	.06		.11			
457.0	460.0	74695	3.0	.0	2H49	4.35	.37	6.35	10.98	90.80				26 7	33	2.69		.12			
460.0	462.5	74696	2.5	.0	2G4	4.55	.11	5.96	7.70	81.50				3 4	8	26.42		.15			
462.5	465.0	74697	2.5	.0	2G4	4.65	.14	5.44	8.84	63.50				2 17	19	25.45		.08			
465.0	467.5	74698	2.5	.0	2F49	5.00	.35	6.43	12.00	54.40				1 29	31	.26		.05			
467.5	470.0	74699	2.5	.0	2F19	5.00	.45	2.11	3.35	26.40				1 31	33	.06		.03			
470.0	472.5	74700	2.5	.0	2E49	4.26	.44	3.52	4.23	33.00				1 34	36	.06		.06			
472.5	475.0	74701	2.5	.0	2E49	4.90	.20	5.58	10.45	42.00				1 31	33	.06		.04			
475.0	477.5	74702	2.5	.0	2E9	4.37	.26	2.07	1.34	14.60				6 31	37	.03		.18			
477.5	480.0	74703	2.5	.0	2E49	4.57	.23	2.39	2.46	20.20				2 35	37	.03		.06			
480.0	482.5	74704	2.5	.0	2E49	4.69	.43	1.90	3.11	23.60				2 35	38	.02		.07			
482.5	485.0	74705	2.5	.0	2E49	4.61	.31	3.09	3.77	26.10				2 33	36	.03		.10			
485.0	487.5	74706	2.5	.0	2E49	4.78	.24	1.88	2.73	19.00				2 35	38	.02		.09			
487.5	492.5	74707	5.0	.0	2E9	4.50	.52	.80	1.72	17.40				6 33	39	.04		.19			
492.5	495.0	74708	2.5	.0	2E9	4.72	.45	.97	1.71	19.20				4 35	39	.01		.13			
495.0	497.5	74709	2.5	.0	2E9	4.78	.51	1.28	2.02	25.80				3 36	40	.01		.13			
497.5	500.0	74710	2.5	.0	2E09	4.61	.13	1.70	1.34	17.10				3 35	38	.01		.10			

DDH: 80-01 UTM-N: 9136.0 UTM-E: 14402.0 UTM-ELEV: 3905.0 TOTAL DEPTH: 584.0 SECTION: 118+000
 RFE: 52 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

-----DEPTHS-----		-----ASSAYS-----																			
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
500.0	502.5	74711	2.5	.0	2E49	4.85	.20	2.38	2.98	21.20			1	36	38	.01		.05			
502.5	505.0	74712	2.5	.0	2E49	4.83	.29	3.48	5.83	33.20			1	34	35	.01		.03			
505.0	507.5	74713	2.5	.0	2F4	4.65	.07	6.50	10.80	45.70			1	30	32	.02		.02			
507.5	510.0	74714	2.5	.0	2F4	4.61	.07	7.53	13.90	57.20			2	28	30	.01		.03			
510.0	514.0	74715	4.0	.0	2F09	4.10	.42	2.22	3.51	17.40			3	28	32	.15		.07			
514.0	518.0	74716	4.0	.0	2F09	4.39	.36	2.43	5.01	21.80			4	29	34	.08		.07			
518.0	524.0	74717	6.0	.0	2F09	4.15	.37	2.95	6.50	24.30			8	23	31	.06		.06			
524.0	526.0	74718	2.0	.0	2B01	2.69	.01	.54	.29	8.10					1	.01		.02			
526.0	528.0	74719	2.0	.0	2B01	2.67	.01	2.40	.53	34.20						.02		.02			
528.0	530.0	74720	2.0	.0	2A4	2.79	.04	.96	4.51	17.70			2		3	.16		.07			
530.0	532.5	74721	2.5	.0	2A4	2.80	.06	1.25	3.84	16.80			2	2	4	.15		.03			
532.5	535.0	74722	2.5	.0	2A4	2.96	.16	1.41	3.06	28.00			3	5	8	.18		.02			
535.0	537.5	74723	2.5	.0	2A01	2.77	.03	.84	2.53	11.80			1	1	3	.21		.02			
537.5	540.0	74724	2.5	.0	2A01	2.76	.02	1.06	2.70	16.80			1		2	.17		.02			
540.0	542.5	74725	2.5	.0	2A01	2.87	.14	1.58	3.52	27.60			3	2	6	.21		.03			
542.5	545.0	74726	2.5	.0	2A0	3.04	.19	.96	1.92	36.00			6	6	13	.14		.04			
545.0	547.5	74727	2.5	.0	2A0	2.77	.08	.96	2.30	15.90			2	2	5	.16		.03			
547.5	550.0	74728	2.5	.0	2A0	2.74	.07	.69	2.52	9.00			3		3	.30		.05			
550.0	552.5	74729	2.5	.0	2A0	2.84	.06	1.04	2.53	14.90			4	1	6	.12		.09			
552.5	555.0	74730	2.5	.0	2A41	2.99	.11	.68	5.99	61.90			3	2	6	.39		.04			
555.0	557.5	74731	2.5	.0	2A41	2.76	.04	.95	2.67	9.90			2	1	4	.20		.05			
557.5	560.0	74732	2.5	.0	2A01	2.79	.05	.63	1.23	13.40			2	1	3	.27		.02			
560.0	562.5	74733	2.5	.0	2A4	2.85	.15	.91	3.18	28.60			3	2	5	.15		.04			
562.5	565.0	74734	2.5	.0	2A4	2.88	.17	.98	3.63	29.20			3	2	5	.20		.04			
565.0	567.5	74735	2.5	.0	2A0	2.96	.29	.32	2.65	18.00			4	6	11	.15		.03			
567.5	570.0	74736	2.5	.0	2A0	3.10	.17	.61	2.42	22.10			5	8	13	.13		.03			
570.0	572.5	74737	2.5	.0	2A4	2.97	.14	.68	3.37	21.80			4	4	8	.17		.03			
572.5	575.0	74738	2.5	.0	2A4	2.87	.14	1.30	2.65	24.90			2	2	5	.12		.03			
575.0	577.5	74739	2.5	.0	2A0	2.84	.14	.97	2.22	25.20			2	2	5	.15		.02			
577.5	580.0	74740	2.5	.0	2A0	2.78	.09	.49	.75	11.20			2	2	4	.33		.02			
580.0	584.0	74741	4.0	.0	2A0	2.76	.10	.90	1.70	14.60			1	1	3	.18		.02			

DDH: 80-02 UTM-N: 8305.7 UTM-E: 14914.5 UTM-ELEV: 4061.2 TOTAL DEPTH: 680.0 SECTION: 125
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
465.0	468.0	74747	3.0	.0	2A0	2.98	.11	.04	.14	2.20			4	7	11	.34		.13			
468.0	471.0	74748	3.0	.0	2C0	3.56	.07	.01	.08	1.89			1	21	22	.04		.02			
471.0	473.5	74749	2.5	.0	2E1	3.62	.08	.35	3.95	4.40			.07	1	21	23	.01	.05			
473.5	476.0	74750	2.5	.0	2E1	3.43	.14	.29	2.83	4.70			.14	1	18	19	.02	.05			
476.0	478.5	74751	2.5	.0	2F4	3.54	.11	3.62	6.34	26.69		5.40	2	17	20	.02		.07			
478.5	481.0	74752	2.5	.0	2F4	3.60	.07	4.41	10.71	33.89		.27	2	14	16	.48		.02			
481.0	483.5	74753	2.5	.0	2F4	3.72	.10	8.89	14.99	71.79		.07	3	8	11	.14		.02			
483.5	486.0	74754	2.5	.0	2G4	4.41	.05	3.99	7.78	42.29		.14	1	13	15	33.95		.05			
486.0	488.5	74755	2.5	.0	2G4	4.67	.08	6.73	7.57	119.99		.07	2	13	16	31.39		.23			
488.5	491.0	74756	2.5	.0	2G74	4.30	.20	3.85	8.58	75.29		.13	9	16	25	11.91		.28			
528.0	531.0	74758	3.0	.0	2H4	3.97	.31	2.95	4.48	49.50		.01	19	17	37	.07		.14			
531.0	533.5	74759	2.5	.0	2H4	4.20	.32	2.72	5.04	45.10		.07	21	19	40	.05		.07			
533.5	536.0	74760	2.5	.0	2H4	4.24	.29	4.02	5.58	64.70		.07	22	18	40	.02		.07			
536.0	538.5	74761	2.5	.0	2H0	4.09	.22	.75	1.25	13.40		.14	13	24	37	.01		.11			
538.5	541.0	74762	2.5	.0	2E4	4.30	.11	1.52	2.83	30.80		.27	6	29	36	.01		.16			
541.0	543.5	74763	2.5	.0	2C7	3.89	.20	.93	.24	26.39			13	15	28	.02		.38			
543.5	546.0	74764	2.5	.0	2C7	3.49	.23	.57	.36	13.09			12	16	28	.01		.46			
546.0	548.5	74765	2.5	.0	2C7	3.47	.23	.38	.34	10.30			10	16	27	.02		.35			
548.5	551.0	74766	2.5	.0	2C7	3.41	.29	.54	.49	10.59			9	15	24	.01		.34			
551.0	553.5	74767	2.5	.0	2C7	3.43	.34	.34	.48	13.99			10	16	26	.01		.41			
553.5	556.5	74768	3.0	.0	2D7	4.13	.40	2.50	4.11	36.39		.69	11	22	34	.01		.40			
556.5	559.5	74769	3.0	.0	2E47	4.25	.39	2.83	4.76	41.70		.14	14	25	39	.01		.34			
559.5	562.5	74770	3.0	.0	2E4	4.33	.20	2.56	3.72	42.00		.07	6	29	35	.01		.24			
562.5	565.0	74771	2.5	.0	2F4	4.74	.10	4.88	6.37	48.79		.07	2	34	36	.01		.05			
565.0	568.0	74772	3.0	.0	2F4	4.75	.05	5.32	8.32	46.00		.01	2	33	35	.01		.05			
568.0	571.0	74773	3.0	.0	2E4	4.51	.14	2.37	5.95	25.80		.01	5	31	36	.02		.11			
571.0	573.5	74774	2.5	.0	2F4	3.91	.17	4.50	6.95	32.29		.07	9	18	27	.02		.19			
573.5	576.0	74775	2.5	.0	2C0	3.18	.14	.39	.53	6.79		.07	5	10	16	.17		.05			
576.0	578.5	74776	2.5	.0	2C0	3.08	.20	.27	.58	4.40		.07	5	8	14	.38		.07			
578.5	581.0	74777	2.5	.0	2D0	3.02	.14	1.53	3.83	15.59		.07	4	4	9	.40		.04			
581.0	583.5	74778	2.5	.0	2D0	3.22	.16	1.71	3.33	19.30		.01	5	9	15	.23		.04			
583.5	586.0	74779	2.5	.0	2D0	3.12	.20	1.29	3.29	19.60		.07	5	7	12	.47		.04			
586.0	588.5	74780	2.5	.0	2D0	3.22	.22	2.64	1.71	37.60		.07	7	8	16	.27		.07			
588.5	591.0	74781	2.5	.0	2C07	3.25	.22	3.35	.10	43.89		.07	10	9	19	.11		.10			
591.0	593.5	74782	2.5	.0	2C0	3.16	.17	.23	.83	6.79		.01	6	9	15	.28		.05			
593.5	596.0	74783	2.5	.0	2H4	4.38	.23	4.21	7.12	45.10		.07	15	19	34	.04		.13			
596.0	600.0	74784	4.0	.0	2F4	4.51	.11	4.61	10.18	33.29		.14	3	26	29	.04		.08			
600.0	606.0	74785	6.0	.0	2F0	4.33	.17	3.60	5.46	34.20		.07	4	26	30	.02		.31			
606.0	610.0	74786	4.0	.0	2F8	4.42	.32	4.04	4.50	47.29		.07	19	16	36	.04		.11			
610.0	613.0	74787	3.0	.0	2D4	3.37	.38	2.49	8.68	82.70		.21	5	6	11	.11		.07			
613.0	615.0	74788	2.0	.0	2D0	3.91	.11	2.27	3.62	25.80		.07	6	21	28	.10		.11			
615.0	618.0	74789	3.0	.0	2D4	4.29	.35	8.22	12.42	87.70		.21	16	13	30	.02		.08			
618.0	621.0	74790	3.0	.0	2D0	3.47	.23	1.02	5.05	19.60		.14	6	14	20	.11		.08			
621.0	623.5	74791	2.5	.0	2D0	4.17	.04	3.22	6.33	30.49		.07	1	25	27	.07		.02			
623.5	626.0	74792	2.5	.0	2A4	2.85	.05	1.29	4.15	12.40		.14		3	4	.40		.01			
626.0	628.5	74793	2.5	.0	2A4	3.08	.11	3.25	7.86	41.39		.41	1	5	7	.16		.01			
628.5	631.0	74794	2.5	.0	2A4	2.24	.05	2.79	9.83	24.89		.27	2	3	6	.14		.02			
631.0	633.5	74795	2.5	.0	2A4	4.15	.05	1.56	5.53	22.69		.34	1	6	7	.14		.02			
633.5	636.0	74796	2.5	.0	2A4	2.99	.07	2.41	5.42	33.60		.41	2	5	8	.16		.02			
636.0	638.5	74797	2.5	.0	2A4	3.24	.19	7.67	5.74	59.70		.27	4	5	9	.13		.02			

DDH: 80-02 UTM-N: 8305.7 UTM-E: 14914.5 UTM-ELEV: 4061.2 TOTAL DEPTH: 680.0 SECTION: 125
RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Pc %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
638.5	641.0	74798	2.5	.0	2A4	2.91	.08	3.24	5.58	33.29		.69	2	3	5	.13			.02		
641.0	643.5	74799	2.5	.0	2A0	2.85	.08	1.47	2.19	19.00		.55	2	4	7	.16			.01		
643.5	646.0	74800	2.5	.0	2A0	2.91	.11	.65	.46	14.30		.41	2	5	7	.14			.02		
646.0	648.5	74801	2.5	.0	2A0	2.98	.13	1.33	2.25	22.10		.55	3	4	8	.13			.04		
648.5	651.0	74802	2.5	.0	2A0	2.77	.08	.36	.59	9.90			3	2	6	.13			.02		
651.0	653.5	74803	2.5	.0	2A0	2.89	.08	.11	.49	3.39			2	3	6	.14			.02		
653.5	656.0	74804	2.5	.0	2A0	2.93	.10	.28	.65	5.90			3	6	9	.16			.02		
656.0	658.5	74805	2.5	.0	2A0	2.89	.14	.28	.36	6.79			3	3	6	.14			.02		
658.5	661.0	74806	2.5	.0	2A0	2.75	.11	.20	.33	6.50			1	1	3	.34			.02		
661.0	663.5	74807	2.5	.0	2A0	2.74	.05	.58	1.47	13.99			1	1	3	.20			.02		
663.5	666.0	74808	2.5	.0	2A4	3.58	.07	1.23	3.83	18.00		.14	1	1	3	.14			.04		
666.0	668.5	74809	2.5	.0	2A4	2.19	.05	1.62	4.69	22.69		.14	1		2	.11			.02		
668.5	671.0	74810	2.5	.0	2A4	2.68	.08	1.68	3.06	34.20		.21	1		2	.14			.01		
671.0	673.5	74811	2.5	.0	2A0	2.83	.17	.84	.72	21.80			3	4	7	.14			.02		
673.5	676.0	74812	2.5	.0	2A0	2.87	.14	.28	.65	19.30			3	3	6	.14			.02		
676.0	678.5	74813	2.5	.0	2A0	2.83	.22	.39	.40	33.00			3	4	8	.17			.02		

DDH: 80-03 UTM-N: 8299.4 UTM-E: 15116.6 UTM-ELEV: 4086.3 TOTAL DEPTH: 663.0 SECTION: 126
 RFE: S2 RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	---ASSAYS---													
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %
421.0	423.5	74818	2.5	.0	2C6	3.18	.27	.34		12.80				3 13	17	.27		.08		
423.5	426.0	74819	2.5	.0	2C6	2.96	.13	.12		5.60				1 8	10	.29		.05		
426.0	428.5	74820	2.5	.0	2C6	3.26	.16	.43	.47	9.30				2 16	19	.13		.12		
428.5	431.0	74821	2.5	.0	2C6	3.38	.07	.14	.24	13.40				20 21		.10		.03		
431.0	433.5	74822	2.5	.0	2C6	3.46	.09	.11	.40	7.80				2 21	23	.06		.05		
433.5	436.0	74823	2.5	.0	2C6	3.69	.17	.52	.43	10.00				5 24	29	.05		.18		
436.0	438.5	74824	2.5	.0	2C6	3.39	.13	.35	.34	10.60				2 20	22	.10		.07		
438.5	440.0	74825	1.5	.0	2C6	3.93	.16	.18	.28	13.40				28 29		.10		.02		
440.0	442.5	74826	2.5	.0	2A0	3.38	.13	.14	.15	12.40				19 20		.13		.02		
442.5	445.0	74827	2.5	.0	2A0	3.38	.22	.12	.09	7.20				1 19	21	.10		.02		
445.0	447.5	74828	2.5	.0	2C6	3.66	.18	.10	.20	6.80				2 24	26	.07		.05		
447.5	450.0	74829	2.5	.0	2D4	3.59	.11	4.65	7.98	37.60		.14	2 16	18		.15		.06		
450.0	452.5	74830	2.5	.0	2D4	4.64	.04	4.93	8.56	42.90		.01	1 24	26	16.41			.03		
452.5	455.0	74831	2.5	.0	2D4	4.73	.03	4.20	6.93	44.80		.07		30 31	10.58					
455.0	457.5	74832	2.5	.0	2F4	4.71	.03	5.90	8.88	64.10		.07	1 33	35		.32		.02		
457.5	460.0	74833	2.5	.0	2F4	4.49	.27	6.43	8.90	75.30		.07	1 30	32		.53		.03		
460.0	462.0	74834	2.0	.0	2EC	4.17	.22	.78	1.99	10.90		.07		34 35		.08		.04		
462.0	464.0	74835	2.0	.0	2EC	4.18	.05	.40	1.60	9.00				31 32		.09		.05		
464.0	467.0	74836	3.0	.0	2C5	3.14	.10	.29	.84	5.60			1 14	16		.44		.07		
467.0	469.0	74837	2.0	.0	1D4	2.89	.13	.15	.10	5.30			2 3	6	1.16			.11		
469.0	471.0	74838	2.0	.0	2C5	3.22	.09	.48	.57	8.40			1 15	17		.39		.08		
471.0	473.0	74839	2.0	.0	2F4	4.45	.16	5.29	7.35	82.70		.27	4 26	31		.50		.13		
505.0	508.0	74841	3.0	.0	2E4	4.08	.09	3.20	4.60	76.80		.07	2 27	30		.87		.15		
508.0	511.0	74842	3.0	.0	2E4	3.71	.17	4.51	1.04	124.70		.27	10 17	28		.22		.21		
511.0	514.0	74843	3.0	.0	2E7	4.35	.41	1.02	.52	32.00		.14	21 21	42		.07		.23		
514.0	516.0	74844	2.0	.0	1D4	3.25	.25	3.80	.74	136.50		.75	9 12	21		.26		.18		
516.0	518.0	74845	2.0	.0	2CE	3.46	.20	1.50	.33	47.60			12 13	25		.08		.13		
518.0	520.0	74846	2.0	.0	2CE	3.37	.35	.52	.27	24.60			12 12	25		.06		.16		
520.0	522.5	74847	2.5	.0	2E74	4.38	.09	4.21	2.09	111.30		.55	11 27	39		.07		.13		
522.5	525.0	74848	2.5	.0	2E0	4.61	.09	1.42	.76	20.50			2 36	39		.05		.10		
525.0	527.5	74849	2.5	.0	2E0	4.58	.20	1.03	.51	13.70			3 37	40		.05		.15		
527.5	530.0	74850	2.5	.0	2F0	4.41	.12	1.50	.98	15.90			3 36	39		.05		.12		
530.0	532.5	74851	2.5	.0	2E0	4.60	.17	1.92	1.43	24.30		.01	5 34	39		.06		.18		
532.5	535.0	74852	2.5	.0	2E4	4.79	.34	3.25	2.69	39.20			5 34	39		.06		.23		
535.0	537.5	74853	2.5	.0	2E0	4.43	.15	2.81	1.26	36.40		.07	2 36	38		.04		.07		
537.5	540.0	74854	2.5	.0	2E0	3.38	.20	2.20	1.29	25.80		.14	4 32	36		.05		.17		
540.0	542.5	74855	2.5	.0	2E4	4.88	.24	4.01	4.59	54.10			7 31	38		.06		.38		
542.5	545.0	74856	2.5	.0	2E0	4.63	.39	1.67	2.10	28.00		.07	6 34	41		.06		.30		
545.0	547.5	74857	2.5	.0	2E4	4.60	.26	2.43	2.16	35.50		.14	6 32	39		.05		.37		
547.5	550.0	74858	2.5	.0	2E4	4.24	.24	2.00	2.74	36.40		.14	8 28	36		.04		.44		
550.0	552.5	74859	2.5	.0	2E1	4.05	.14	1.80	1.48	23.00		.07	6 27	34		.05		.28		
552.5	555.0	74860	2.5	.0	2E1	4.41	.09	.36	.29	11.20			2 35	38		.05		.03		
555.0	557.5	74861	2.5	.0	2E1	4.25	.20	.38	.27	13.70			5 30	36		.04		.08		
557.5	560.0	74862	2.5	.0	2E1	4.10	.25	.43	.43	13.10			4 31	35		.05		.04		
560.0	562.5	74863	2.5	.0	2E4	4.20	.25	3.08	2.47	52.60		.14	7 26	33		.06		.13		
562.5	565.0	74864	2.5	.0	2E4	4.30	.28	3.00	5.00	51.60		.07	8 27	36		.08		.27		
565.0	567.5	74865	2.5	.0	2E0	4.33	.13	1.77	2.21	22.10		.14	4 32	36		.10		.12		
567.5	570.0	74866	2.5	.0	2E4	4.14	.19	2.23	3.73	25.20			5 34	39		.12		.22		
570.0	572.5	74867	2.5	.0	2E4	4.34	.24	2.46	3.31	19.90		.07	6 29	36		.05		.37		
572.5	575.0	74868	2.5	.0	2E4	4.36	.18	3.00	7.09	32.30		.21	4 30	34		.05		.18		

DDH: 80-03 UTM-N: 8299.4 UTM-E: 15116.6 UTM-ELEV: 4086.3 TOTAL DEPTH: 663.0 SECTION: 126
RFE: S2 RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
575.0	577.5	74869	2.5	.0	2E4	4.59	.22	5.15	6.08	31.40		.14	3	31	35	.04		.14			
577.5	582.5	74870	5.0	.0	2E4	4.30	.18	2.35	3.42	10.60		.07	5	28	33	.05		.23			
582.5	585.0	74871	2.5	.0	2E4	4.07	.12	1.86	2.84	21.80		.01	4	28	32	.04		.17			
585.0	587.5	74872	2.5	.0	2F0	4.91	.03	2.73	6.32	25.80		.07		38	38	.04		.04			
587.5	590.0	74873	2.5	.0	2F4	4.60	.04	4.39	7.93	28.00		.01	1	34	36	.05		.04			
590.0	595.0	74874	5.0	.0	2F4	4.56	.07	3.44	7.49	21.20		.07	1	33	35	.05		.06			
595.0	600.0	74875	5.0	.0	2F4	5.04	.04	2.88	6.63	17.40		.01	1	38	39	.04		.02			
600.0	602.5	74876	2.5	.0	2C0	3.07	.11	.58	1.95	6.20			5	8	14	.33		.06			
602.5	605.0	74877	2.5	.0	2D0	3.23	.16	1.64	4.88	21.20		.14	6	9	16	.15		.10			

DDH: 80-04 UTM-N: 8513.9 UTM-E: 15126.1 UTM-ELEV: 4109.2 TOTAL DEPTH: 704.0 SECTION: 125
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

---DEPTHS---		SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														S.G. W.R.
FROM	TO					Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	
582.5	585.0	74883	2.5	.0 2F6	4.53	.04	4.43	7.47	69.00		.07	2	25	27	8.72		.05			
610.5	613.0	74886	2.5	.0 2E84	4.43	.13	3.64	3.45	47.00		.21	6	28	35	.18		.24			
613.0	615.5	74887	2.5	.0 2E4	4.57	.08	2.57	2.69	21.80		.07	2	36	38	.10		.06			
615.5	618.0	74888	2.5	.0 2E0	4.18	.03	.87	.55	7.20		.07		36	37	.11		.01			
618.0	620.5	74889	2.5	.0 2E4	4.34	.07	1.59	2.51	11.20		.07	1	35	36	.10		.01			
620.5	624.0	74890	3.5	.0 2A0	3.98	.01	.44	.80	3.70			1	31	33	.05		.01			
624.0	628.0	74891	4.0	.0 2EC	3.79	.02	1.30	2.38	6.80		.07	1	27	28	.10		.03			
628.0	630.5	74892	2.5	.0 2ED	3.43	.18	1.39	3.50	11.20			4	15	20	.18		.14			
630.5	633.0	74893	2.5	.0 2ED	4.04	.18	3.13	6.83	10.00			5	23	28	.12		.10			
633.0	635.5	74894	2.5	.0 2ED	3.91	.24	3.87	9.44	12.10			6	17	24	.08		.08			
635.5	638.0	74895	2.5	.0 2A1	2.96	.11	.87	3.05	10.90		.14	3	4	8	.28		.03			
638.0	641.5	74896	3.5	.0 2A1	2.90	.06	1.10	2.06	12.40		.14	2	3	5	.31		.03			
641.5	645.0	74897	3.5	.0 2A1	2.77	.05	.82	1.84	10.30		.07	2	1	3	.34		.03			
645.0	648.5	74898	3.5	.0 2A1	2.74	.05	.74	1.81	8.70		.14	1	1	2	.33		.03			
648.5	651.0	74899	2.5	.0 2C5	2.95	.21	2.56	1.08	37.90		.41	3	4	8	.45		.03			
651.0	653.5	74900	2.5	.0 2C5	2.89	.13	1.00	1.16	9.60			6	4	11	.24		.08			
653.5	656.0	74901	2.5	.0 2C5	2.92	.17	.74	.89	8.10			5	3	8	.30		.07			
656.0	658.5	74902	2.5	.0 2C5	3.02	.20	.54	1.43	6.80			6	5	12	.24		.06			
658.5	661.0	74903	2.5	.0 2D4	3.48	.27	4.51	9.86	43.50		.07	7	9	17	.12		.04			
661.0	663.5	74904	2.5	.0 2A1	2.88	.13	1.20	.84	24.30			3	5	8	.24					
663.5	666.0	74905	2.5	.0 2A1	2.77	.09	.33	.64	10.30			2	2	4	.27		.02			
666.0	668.5	74906	2.5	.0 2A1	2.83	.14	.29	.89	15.60			2	3	5	.24		.04			
668.5	671.0	74907	2.5	.0 2A1	2.81	.10	.51	.79	16.80			1	3	5	.19		.04			

DDH: 80-06 UTM-N: 8859.7 UTM-E: 14928.0 UTM-ELEV: 4027.5 TOTAL DEPTH: 753.0 SECTION: 122+020
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	ASSAYS														
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
459.0	461.5	74950	2.5	.0	2E41	4.22	.08	3.61	7.69	64.70			3	23	27	3.28		.06			
461.5	463.5	74951	2.0	.0	2E41	4.69	.08	3.00	4.08	50.40			7	25	33	4.20		.08			
478.5	481.5	74953	3.0	.0	2H9	4.37	.51	4.22	2.51	93.60			21	11	33	.69		.25			
481.5	484.5	74954	3.0	.0	2E41	4.00	.19	3.98	3.33	66.20			5	27	33	3.63		.26			
484.5	488.5	74955	4.0	.0	2G4	4.07	.14	4.71	4.85	79.60			2	23	26	11.06		.15			
488.5	492.5	74956	4.0	.0	2E4	4.26	.17	4.28	3.93	47.60			1	32	34	2.84		.08			
492.5	495.0	74957	2.5	.0	2C3	3.54	.01	.17	.05	6.20				28	28	.02		.06			
495.0	497.0	74958	2.0	.0	2C3	3.86	.01	.16	.06	7.80				32	32	.02		.01			
497.0	499.0	74959	2.0	.0	2E1	4.63	.02	.40	.20	8.70				37	38	.01		.02			
499.0	501.5	74960	2.5	.0	2E1	3.96	.09	.69	.62	9.30			1	32	34	.01		.04			
501.5	504.0	74961	2.5	.0	2E4	4.28	.19	2.65	2.56	26.40			4	28	33	.06		.23			
504.0	506.5	74962	2.5	.0	2E1	4.15	.12	1.08	1.61	13.70			3	30	33	.34		.12			
506.5	509.0	74963	2.5	.0	2E1	4.32	.10	.88	.47	19.60			1	33	35	.42		.04			
509.0	512.5	74964	3.5	.0	2G9	4.75	.24	2.51	4.66	31.40			1	26	27	15.80		.04			
512.5	515.0	74965	2.5	.0	2E69	4.63	.21	1.61	2.89	22.40			2	29	32	5.84		.11			
515.0	517.5	74966	2.5	.0	2G0	4.43	.10	2.34	4.16	27.70			1	20	22	18.26		.08			
517.5	520.0	74967	2.5	.0	2G0	4.73	.15	2.59	4.71	29.90			2	25	27	12.67		.14			
520.0	522.5	74968	2.5	.0	2G0	4.41	.06	2.06	6.85	23.30				11	12	40.84		.03			
522.5	525.0	74969	2.5	.0	2G40	4.51	.16	3.64	6.01	44.80			2	16	18	29.87		.16			
525.0	527.5	74970	2.5	.0	2E6	4.53	.04	1.32	1.92	25.20				34	35	3.12		.02			
527.5	530.0	74971	2.5	.0	2G0	4.60	.07	3.56	5.71	41.70			1	24	26	15.80		.07			
530.0	532.5	74972	2.5	.0	2E48	4.35	.35	3.72	3.10	42.60			4	33	38	.24		.17			
532.5	535.0	74973	2.5	.0	2E1	4.57	.19	1.80	1.71	23.60			1	38	39	.02		.05			
535.0	540.0	74974	5.0	.0	2E41	4.74	.09	3.25	2.54	37.60			1	38	40	.04		.04			
540.0	542.5	74975	2.5	.0	2E1	4.40	.02	.22	.10	9.30				38	39	.01					
542.5	545.0	74976	2.5	.0	2E1	4.51	.03	.16	.09	8.40				39	39	.02		.01			
545.0	547.5	74977	2.5	.0	2E1	4.38	.06	.30	.16	10.60				40	41	.01		.01			
547.5	550.0	74978	2.5	.0	2E41	4.88	.14	2.19	2.27	29.20				35	36	2.29		.04			
550.0	552.5	74979	2.5	.0	2E41	4.90	.09	1.76	2.46	23.30				40	41	.02		.01			
552.5	555.0	74980	2.5	.0	2E1	4.30	.14	.88	.48	19.90				37	37	.04		.01			
555.0	557.5	74981	2.5	.0	2E1	4.70	.06	1.13	.34	24.60				37	38			.01			
557.5	560.0	74982	2.5	.0	2E41	5.11	.06	6.50	4.70	71.80			1	36	37	.01		.05			
560.0	562.5	74983	2.5	.0	2E41	5.23	.07	4.53	2.61	39.20				39	40	.01		.03			
562.5	565.0	74984	2.5	.0	2E1	4.42	.05	1.46	.88	15.60				38	39	.01		.01			
565.0	567.5	74985	2.5	.0	2E1	4.30	.10	1.09	1.28	15.90				37	38	.01		.02			
567.5	570.0	74986	2.5	.0	2E48	4.97	.37	6.38	5.31	95.80			5	31	37	.73		.29			
570.0	572.5	74987	2.5	.0	2E49	4.74	.33	3.48	4.23	47.60			5	34	39	.24		.26			
572.5	575.0	74988	2.5	.0	2E4	4.80	.12	3.48	2.64	40.70			2	36	38			.07			
575.0	577.5	74989	2.5	.0	2E49	4.54	.40	3.89	1.37	80.20			2	33	35	.04		.05			
577.5	580.0	74990	2.5	.0	2E1	4.16	.19	1.54	2.37	27.70			1	33	34	.03		.02			
580.0	582.5	74991	2.5	.0	2E1	4.58	.13	.54	.92	15.90			1	39	40			.02			
585.0	587.5	74993	2.5	.0	2E1	4.64	.07	1.36	1.10	22.40				36	37			.01			
587.5	591.0	74994	3.5	.0	2E1	4.76	.04	.44	.14	13.70				5	6			.02			
591.0	593.5	74995	2.5	.0	2C39	3.89	.26	.40	.48	54.70				28	29	.01		.01			
593.5	596.0	74996	2.5	.0	2E1	4.49	.05	.25	.21	14.30				35	35	.01		.01			
596.0	598.0	74997	2.0	.0	2E4	5.07	.02	3.42	3.33	28.30				36	36	.01		.01			
598.0	601.0	74998	3.0	.0	2E41	3.40	.08	2.37	7.00	37.00				17	18	.03		.02			
601.0	603.5	74999	2.5	.0	2E1	4.74	.18	.87	1.18	14.00				36	37	.02		.01			
603.5	606.0	75000	2.5	.0	2E41	4.04	.15	1.67	2.78	16.80			1	29	30	.04		.03			

DDH: 80-06 UTM-N: 8859.7 UTM-E: 14928.0 UTM-ELEV: 4027.5 TOTAL DEPTH: 753.0 SECTION: 122+020
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	---ASSAYS---													
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %
606.0	608.5	75001	2.5	.0	2E19	4.58	.38	1.74	2.15	17.70			4	30	34			.11		
608.5	611.0	75002	2.5	.0	2E1	3.83	.14	.85	1.01	22.70			1	29	30	.02		.02		
611.0	613.0	75003	2.0	.0	2E19	3.96	.26	.40	1.36	15.60			2	26	29	.03		.09		
613.0	616.0	75004	3.0	.0	2E89	4.30	.33	.33	1.97	7.80			9	27	36			.44		
616.0	619.0	75005	3.0	.0	2E48	4.30	.28	1.45	3.04	10.30			8	28	36	.01		.33		
619.0	621.5	75006	2.5	.0	2F49	4.46	.39	3.33	7.82	19.00			6	26	32	.02		.24		
621.5	624.0	75007	2.5	.0	2F49	4.35	.26	4.58	7.67	20.80			5	37	42	.03		.18		
624.0	626.5	75008	2.5	.0	2F4	4.70	.14	3.60	8.75	22.70			3	29	33	.01		.10		
626.5	629.0	75009	2.5	.0	2F9	4.43	.37	1.96	4.39	15.60			4	28	33	.01		.16		
629.0	631.5	75010	2.5	.0	2F4	4.80	.05	5.16	8.69	48.50			2	31	33	.01		.05		
631.5	634.0	75011	2.5	.0	2F4	4.90	.06	5.72	10.71	28.90			3	27	31			.06		
634.0	636.5	75012	2.5	.0	2F49	4.12	.26	5.73	12.20	34.20			5	20	25	.01		.09		
636.5	639.0	75013	2.5	.0	2F4	4.97	.05	4.87	10.07	28.60			2	31	33	.01		.03		
639.0	641.5	75014	2.5	.0	2F4	4.73	.06	7.30	12.40	42.30			2	28	31	.01		.03		
641.5	644.0	75015	2.5	.0	2F4	4.76	.05	6.86	10.50	39.50			1	31	33			.02		
644.0	646.5	75016	2.5	.0	2F4	5.00	.03	6.83	10.50	39.50			1	31	33	.01		.02		
646.5	649.0	75017	2.5	.0	2F4	4.80	.01	8.37	14.90	45.70			1	27	29	.01		.02		
649.0	651.5	75018	2.5	.0	2D5	3.48	.12	1.26	3.52	27.40			1	19	21	.03		.02		
651.5	654.0	75019	2.5	.0	2D5	3.49	.06	.87	3.52	16.50			1	16	17	.06		.01		
654.0	656.5	75020	2.5	.0	2D45	3.32	.17	4.86	7.07	44.80			2	12	15	.06		.02		
656.5	659.0	75021	2.5	.0	2C5	3.49	.04	.21	2.29	13.40			1	17	19	.06		.02		
659.0	661.5	75022	2.5	.0	2C5	3.55	.03	.40	2.98	20.50			1	20	22	.06		.01		
661.5	664.0	75023	2.5	.0	2D5	3.54	.02	1.42	3.95	16.50			1	18	19	.04		.01		
664.0	666.5	75024	2.5	.0	2D4	3.28	.04	7.18	2.82	55.10			1	20	21	.08		.01		
666.5	669.0	75025	2.5	.0	2D4	3.27	.08	6.32	14.05	32.00			2	8	10	.06		.01		
669.0	671.5	75026	2.5	.0	2D4	3.49	.03	8.20	16.00	36.70			2	8	10	.07		.01		
671.5	674.0	75027	2.5	.0	2D4	3.61	.02	9.60	16.37	36.70			2	9	12	.06		.01		
674.0	676.5	75028	2.5	.0	2D4	3.69	.03	10.15	18.26	39.80			2	9	11	.06		.01		
676.5	679.0	75029	2.5	.0	2D4	3.43	.03	5.15	16.21	25.20			2	9	11	.06		.01		
679.0	681.5	75030	2.5	.0	2D4	3.49	.02	10.20	17.22	41.40			2	8	11	.07		.01		
681.5	684.0	75031	2.5	.0	2D4	3.31	.03	6.04	15.18	24.60			2	6	8	.11		.01		
684.0	686.5	75032	2.5	.0	2D4	3.68	.04	10.63	18.79	33.30			3	7	10	.07		.02		
686.5	689.0	75033	2.5	.0	2D4	3.81	.02	7.33	15.98	23.90			2	12	15	.04		.01		
689.0	691.5	75034	2.5	.0	2D4	3.53	.04	6.40	14.95	20.50			2	11	13	.06		.01		
691.5	694.0	75035	2.5	.0	2D4	3.80	.02	7.42	15.92	28.30			2	13	15	.03		.01		
694.0	696.5	75036	2.5	.0	2D4	3.50	.02	5.74	14.05	21.20			2	11	13	.08		.01		
696.5	699.0	75037	2.5	.0	2D4	3.41	.17	6.46	13.96	33.00			4	8	12	.10		.03		
699.0	701.5	75038	2.5	.0	2D4	5.87	.10	5.14	13.03	32.70			3	13	16	.08		.05		
701.5	704.0	75039	2.5	.0	2D0	3.20	.07	.78	7.72	44.80			2	11	14	.10		.05		
704.0	706.5	75040	2.5	.0	2D4	3.32	.12	4.37	6.86	36.40			6	15	21	.07		.07		
706.5	709.0	75041	2.5	.0	2D4	3.15	.16	3.95	8.65	29.90			5	6	11	.09		.09		
709.0	711.5	75042	2.5	.0	2A0	2.96	.19	.70	2.54	14.30			6	4	10	.18		.05		
711.5	714.6	75043	3.1	.0	2B0(	2.95	.14	.35	.15	13.10			1	3	5	.01		.01		
714.6	717.8	75044	3.2	.0	2B4*	3.05	.11	7.63	3.04	114.10			2	2	5	.03		.11		
717.8	721.0	75045	3.2	.0	2B4*	3.13	.16	3.87	12.10	24.90			5	3	8	.07		.13		
721.0	723.5	75046	2.5	.0	2D47	3.50	.40	4.66	13.73	28.00			13	2	15	.08		.08		
723.5	726.0	75047	2.5	.0	2D47	3.36	.34	2.29	10.72	19.90			13	4	17	.06		.09		
726.0	728.0	75048	2.0	.0	2D79	3.40	.27	1.89	4.64	26.70			19	2	22	.07		.11		

DDH: 80-07 UTM-N: 8674.8 UTM-E: 14718.2 UTM-ELEV: 4031.2 TOTAL DEPTH: 699.0 SECTION: 122+020
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

-----DEPTHS-----						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
451.0	453.0	75054	2.0	.0	2C39	3.18	.21	.25	.07	2.80			9	11	21	.54		.06			
453.0	455.0	75055	2.0	.0	2C39	3.86	.29	.36	.12	13.40			19	16	35	.14		.14			
455.0	457.5	75056	2.5	.0	2F49	4.45	.22	7.79	6.31	127.20			9	21	31	.19		.77			
457.5	460.0	75057	2.5	.0	2F4	4.44	.14	8.42	8.15	133.70			7	22	29	.55		.53			
474.0	477.0	75059	3.0	.0	2H9	4.27	.34	2.37	1.70	71.20			31	9	41	.18		.33			
477.0	480.0	75060	3.0	.0	2G0	2.87	.04	.11	.30	5.60			2	2	5	11.24		.05			
480.0	483.0	75061	3.0	.0	2G0	3.06	.05	.78	1.33	14.90			3	2	5	23.20		.10			
483.0	486.5	75062	3.5	.0	2G0	3.60	.35	3.45	3.76	66.60			6	8	15	18.81		.19			
486.5	489.0	75063	2.5	.0	2H49	4.41	.26	7.76	7.70	165.50			19	15	34	.57		.43			
489.0	491.5	75064	2.5	.0	2D0	3.52	.18	3.75	6.19	81.20			11	12	23	2.71		.22			
491.5	494.0	75065	2.5	.0	2D0	3.05	.09	1.29	3.26	28.00			5	6	12	2.58		.08			
494.0	496.5	75066	2.5	.0	2C0	3.03	.11	.33	.98	13.30			6	6	13	3.30		.05			
496.5	499.0	75067	2.5	.0	****	3.09	.08	.50	1.20	8.40			6	6	13	3.80		.02			
499.0	501.5	75068	2.5	.0	2C0	3.02	.11	1.31	2.83	25.50			6	5	11	2.56		.04			
501.5	504.0	75069	2.5	.0	2D0	2.97	.08	1.27	4.09	24.90			5	4	10	.30		.05			
504.0	506.5	75070	2.5	.0	2C0	2.98	.10	.69	1.75	13.40			7	4	11	2.58		.02			
506.5	509.0	75071	2.5	.0	2C0	3.21	.14	2.45	4.74	42.00			13	3	16	2.35		.05			
509.0	511.0	75072	2.0	.0	2H49	4.32	.25	5.25	9.85	61.00			29	7	36	2.28		.08			
511.0	513.5	75073	2.5	.0	2H4	4.54	.15	3.97	6.12	51.00			13	21	34	1.00		.08			
513.5	516.0	75074	2.5	.0	2H9	4.29	.22	2.31	2.59	28.60			16	21	38	.07		.12			
516.0	519.0	75075	3.0	.0	2H9	4.38	.39	3.24	4.06	115.10			18	18	37	.26		.12			
519.0	522.0	75076	3.0	.0	2E41	3.90	.16	8.73	13.70	113.80			18	10	28	.06		.37			
522.0	525.0	75077	3.0	.0	2E41	4.34	.22	8.23	11.10	138.70			17	13	30	.07		.34			
525.0	527.5	75078	2.5	.0	2H9	4.54	.32	3.88	4.31	70.30			36	4	41	3.25		.29			
527.5	531.0	75079	3.5	.0	2E46	4.07	.19	4.56	3.88	79.90			16	20	37	5.32		.28			
545.0	549.5	75081	4.5	.0	2E39	4.00	.30	1.82	.50	28.90			18	23	42	4.65		.19			
549.5	552.0	75082	2.5	.0	2H49	4.34	.44	4.81	6.67	72.50			29	13	43	.05		.26			
552.0	554.0	75083	2.0	.0	2G4	4.37	.13	5.99	8.63	97.70			6	17	24	22.49		.21			
554.0	557.0	75084	3.0	.0	2G4	4.49	.05	6.17	8.73	98.00			2	14	17	40.62		.09			
557.0	560.0	75085	3.0	.0	2G4	4.42	.15	5.65	8.56	85.80			5	15	21	30.82		.16			
560.0	562.5	75086	2.5	.0	2E41	4.66	.04	2.72	3.03	29.20			3	35	39	.18		.10			
562.5	565.0	75087	2.5	.0	2E1	4.63	.05	.93	1.24	9.60			1	39	41	.07		.04			
565.0	567.5	75088	2.5	.0	2E1	4.68	.21	1.90	1.24	17.10			1	39	40	.13		.04			
567.5	570.0	75089	2.5	.0	2E1	4.25	.04	.55	.47	11.50			35	36	.06			.01			
570.0	572.5	75090	2.5	.0	2E1	4.72	.08	.05	.09	9.00			44	45	.05			.01			
572.5	575.0	75091	2.5	.0	2E41	4.70	.04	2.43	4.16	19.30			37	38	7.02			.01			
575.0	577.5	75092	2.5	.0	2E41	4.78	.04	4.05	6.56	32.70			34	35	5.91			.01			
577.5	580.0	75093	2.5	.0	2E41	4.56	.14	2.77	2.31	28.00			1	38	39	.07		.04			
580.0	582.5	75094	2.5	.0	2E41	4.85	.28	3.39	2.59	40.70			1	40	41	.05		.06			
582.5	585.0	75095	2.5	.0	2E1	4.34	.04	.47	.51	11.80			1	36	38	.08		.07			
585.0	587.5	75096	2.5	.0	2E1	3.94	.07	.31	.22	11.50			3	28	32	.04		.05			
587.5	590.0	75097	2.5	.0	2E49	4.20	.34	1.68	2.91	26.10			11	23	35	2.56		.10			
590.0	593.0	75098	3.0	.0	2D9	3.14	.24	2.45	4.73	34.20			7	5	13	.46		.07			
593.0	596.5	75099	3.5	.0	2D9	3.04	.81	1.57	4.21	26.70			4	6	11	.58		.05			
596.5	599.5	75100	3.0	.0	2E4	4.64	.10	3.46	6.13	37.30			5	35	40	.06		.06			
599.5	602.0	75101	2.5	.0	2E4	4.57	.13	5.05	6.71	24.90			4	31	36	.05		.24			
602.0	604.5	75102	2.5	.0	2E4	4.70	.40	6.29	6.46	34.50			2	35	38	.06		.12			
604.5	607.0	75103	2.5	.0	2E49	4.85	.25	5.16	6.12	30.80			1	37	39	.05		.07			
607.0	609.5	75104	2.5	.0	2E4	4.80	.11	3.55	6.40	19.60			1	37	39	.04		.04			

DDH: 80-07 UTM-N: 8674.8 UTM-E: 14718.2 UTM-ELEV: 4031.2 TOTAL DEPTH: 699.0 SECTION: 122+020
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	ASSAYS													
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %
609.5	612.0	75105	2.5	.0	2E4	4.78	.07	3.53	6.32	23.00			4	37	42	.05		.02		
612.0	614.5	75106	2.5	.0	2E49	4.85	.23	1.67	1.96	16.80			1	43	44	.03		.01		
614.5	617.0	75107	2.5	.0	2E4	4.91	.06	2.93	4.70	14.60			1	41	42	.03		.02		
617.0	619.5	75108	2.5	.0	2E4	4.87	.12	2.87	4.80	22.40			1	40	42	.04		.02		
619.5	623.0	75109	3.5	.0	2H9	4.31	.47	3.22	6.61	51.90			41	4	45	.07		.07		
623.0	626.0	75110	3.0	.0	2H9	4.24	.58	2.99	6.31	49.80			41	7	49	.05		.07		
626.0	628.5	75111	2.5	.0	2D49	3.29	.25	3.60	8.05	43.50			8	5	14	.32		.07		
628.5	631.0	75112	2.5	.0	2D49	3.37	.18	9.70	3.55	150.80			6	7	14	.33		.05		
631.0	633.5	75113	2.5	.0	2F9	4.04	.26	4.92	4.45	354.60			6	22	28	.14		.07		
633.5	636.0	75114	2.5	.0	2D0	3.21	.15	1.68	3.67	88.00			3	9	13	.14		.05		
636.0	638.0	75115	2.0	.0	2D0	2.95	.12	1.30	4.33	37.00			4	3	7	.25		.04		
638.0	640.0	75116	2.0	.0	2H0	4.45	.63	3.29	6.15	19.60			35	6	42	.39		.04		
640.0	642.5	75117	2.5	.0	2E4	4.55	.14	4.85	8.68	24.60			4	28	32	.06		.03		
642.5	645.0	75118	2.5	.0	2E4	5.06	.03	4.14	5.61	11.80			2	30	32	.03		.03		
645.0	647.5	75119	2.5	.0	2E4	4.95	.04	4.81	5.22	49.10			3	33	36	.04		.05		
647.5	650.0	75120	2.5	.0	2E4	4.87	.02	6.17	7.29	19.90			3	34	37	.05		.05		
650.0	652.5	75121	2.5	.0	2E4	5.02	.03	3.56	5.07	11.20			1	33	35	.05		.03		
652.5	655.0	75122	2.5	.0	2E4	4.89	.01	7.42	10.18	131.90			2	32	34	.04		.03		
655.0	657.5	75123	2.5	.0	2E4	5.32	.01	6.11	7.01	18.40			1	35	37	.04		.02		
657.5	660.0	75124	2.5	.0	2E4	5.12	.02	5.28	11.30	19.00			2	32	34	.04		.03		
660.0	662.0	75125	2.0	.0	2E41	4.04	.03	3.35	7.44	12.40			1	26	27	.07		.04		
662.0	664.5	75126	2.5	.0	2F41	4.16	.02	4.22	9.12	14.30			1	26	28	.08		.04		
664.5	667.0	75127	2.5	.0	2F41	4.34	.92	6.08	14.80	23.60			2	25	28	.06		.03		
667.0	670.0	75128	3.0	.0	2E41	3.38	.03	1.12	4.68	10.60			1	16	18	.09		.03		
670.0	672.5	75129	2.5	.0	2E41	3.54	.04	2.76	8.43	17.70			2	17	20	.05		.05		
672.5	675.0	75130	2.5	.0	2A41	3.37	.12	4.57	11.30	60.70			3	8	11	.08		.04		
675.0	678.0	75131	3.0	.0	2A41	3.02	.21	3.21	6.49	69.00			3	2	5	.13		.04		
678.0	680.5	75132	2.5	.0	2A41	3.56	.36	1.03	6.62	19.60			8	13	21	.09		.07		
680.5	683.0	75133	2.5	.0	2D39	3.28	.36	1.43	6.69	22.10			6	9	16	.20		.04		
683.0	685.5	75134	2.5	.0	2D39	3.33	.37	.95	6.00	23.00			7	13	20	.18		.04		
685.5	688.0	75135	2.5	.0	2D39	3.43	.50	1.40	3.64	21.50			8	15	24	.15		.08		
688.0	690.5	75136	2.5	.0	2D39	3.22	.29	1.86	7.38	24.30			5	12	17	.16		.04		
690.5	693.0	75137	2.5	.0	2D0	2.98	.18	2.18	5.49	28.60			4	3	7	.30		.01		
693.0	695.5	75138	2.5	.0	2D0	3.00	.16	1.89	7.02	29.90			3	4	8	.36		.06		
695.5	699.0	75139	3.5	.0	2D43	3.35	.28	7.91	5.31	133.10			10	4	15	.17		.02		

DDH: 80-08 UTM-N: 9060.8 UTM-E: 14675.2 UTM-ELEV: 3954.5 TOTAL DEPTH: 601.0 SECTION: 120+000
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
409.0	412.0	75143	3.0	.0	2L14	3.32	.05	4.32	7.78	128.80			4	3	8	15.65		.15			
412.0	414.5	75144	2.5	.0	2D4	3.98	.13	5.55	7.81	111.00			11	14	25	6.89		.26			
414.5	417.0	75145	2.5	.0	2G1	3.07	.10	1.85	2.21	31.70			7	6	14	13.98		.13			
417.0	419.5	75146	2.5	.0	2G4	4.07	.17	4.29	5.84	89.90			14	8	22	16.15		.20			
419.5	422.0	75147	2.5	.0	2D46	3.61	.19	5.30	7.06	128.10			12	12	24	3.05		.33			
422.0	425.0	75148	3.0	.0	2L14	3.22	.19	1.85	2.09	38.60			11	9	20	4.47		.19			
425.0	428.0	75149	3.0	.0	2L14	2.82	.06	.27	.34	6.80			15	5	20	.92		.16			
428.0	430.5	75150	2.5	.0	2D61	3.77	.16	5.71	3.12	128.10			4	12	16	12.98		.14			
430.5	433.0	75151	2.5	.0	2C61	3.03	.22	1.64	.64	37.00			4	5	10	11.48		.13			
433.0	435.5	75152	2.5	.0	2C6	2.97	.10	.42	.33	12.40			3	3	7	8.89		.12			
435.5	437.5	75153	2.0	.0	2C69	3.24	.30	2.06	1.70	38.30			6	12	18	5.47		.32			
437.5	440.0	75154	2.5	.0	2E41	4.57	.29	4.32	3.91	68.70			6	22	28	5.55		.23			
440.0	442.5	75155	2.5	.0	2E09	4.68	.24	4.17	4.11	65.60			5	26	32	7.47		.25			
442.5	445.0	75156	2.5	.0	2E49	5.56	.20	1.91	2.20	29.20			2	37	39	.22		.09			
445.0	447.5	75157	2.5	.0	2E09	4.67	.31	1.95	1.26	25.20			2	33	36	.57		.09			
447.5	450.0	75158	2.5	.0	2E0	4.52	.16	1.34	1.41	18.70			1	36	37	.34		.02			
450.0	452.5	75159	2.5	.0	2E0	4.54	.14	.74	.69	15.20			1	37	39	.10		.04			
452.5	455.0	75160	2.5	.0	2E4	4.15	.06	1.85	2.89	17.70			1	30	32	.45		.03			
455.0	457.5	75161	2.5	.0	2E4	4.71	.16	3.85	5.92	38.30			2	34	36	.10		.07			
457.5	460.0	75162	2.5	.0	2E0	5.89	.12	1.30	.63	19.00				39	40	.45					
460.0	462.5	75163	2.5	.0	2E0	4.03	.12	1.51	.75	21.20				39	40	.57		.01			
462.5	465.0	75164	2.5	.0	2E0	4.47	.09	2.24	1.44	32.00			1	35	36	.10		.01			
465.0	467.5	75165	2.5	.0	2E0	4.22	.13	1.08	.69	17.70			1	34	35	.34		.03			
467.5	470.0	75166	2.5	.0	2E0	4.77	.12	1.82	1.83	27.70			1	39	40	.34		.02			
470.0	472.5	75167	2.5	.0	2E0	4.32	.14	1.64	1.27	26.40			2	32	35	.45		.03			
472.5	475.0	75168	2.5	.0	2E09	3.93	.29	1.84	1.13	33.60			2	32	34	.57		.08			
475.0	478.0	75169	3.0	.0	2E49	4.75	.36	2.50	1.69	48.50			3	35	38	.22		.16			
478.0	481.0	75170	3.0	.0	2E09	3.29	.34	1.68	.66	36.70			3	34	37	.22		.10			
481.0	483.5	75171	2.5	.0	2E6	4.98	.10	.99	1.22	30.80			1	33	35	3.13		.05			
483.5	486.0	75172	2.5	.0	2G4	4.42	.06	2.94	7.60	42.90			1	9	11	20.91		.05			
486.0	488.5	75173	2.5	.0	2E06	4.51	.36	1.52	2.46	26.10			6	30	37	4.80		.29			
488.5	491.0	75174	2.5	.0	2E89	5.64	.46	1.37	1.68	29.20			10	27	38	.22		.30			
491.0	493.5	75175	2.5	.0	2E48	4.50	.40	4.13	4.85	56.90			8	28	37	.10		.34			
493.5	496.0	75176	2.5	.0	2E48	4.64	.19	9.15	3.30	131.90			3	29	32	.10		.12			
496.0	498.5	75177	2.5	.0	2E48	4.45	.33	2.42	4.11	74.30			8	28	37	.34		.39			
498.5	501.5	75178	3.0	.0	2E48	4.35	.32	1.61	3.34	23.00			10	26	37	.22		.46			
501.5	504.5	75179	3.0	.0	2E48	4.61	.40	1.55	2.91	20.50			9	29	39	.69		.45			
504.5	507.0	75180	2.5	.0	2E48	4.71	.25	1.98	3.26	21.20			5	32	37	.22		.38			
507.0	509.5	75181	2.5	.0	2E19	4.80	.44	.82	.43	13.40			1	40	41	.22		.15			
509.5	512.0	75182	2.5	.0	2E1	4.68	.12	1.43	1.79	15.60			2	34	37	.10		.02			
512.0	514.0	75183	2.0	.0	2E41	4.44	.27	2.84	3.88	23.90			6	28	35	.34		.07			
514.0	516.0	75184	2.0	.0	2E48	4.68	.26	1.65	2.51	15.90			4	34	38	.22		.24			
516.0	518.0	75185	2.0	.0	2E48	4.81	.17	2.47	2.98	22.40			4	33	38	.10		.15			
518.0	520.0	75186	2.0	.0	2E89	4.73	.31	.87	2.10	15.60			8	31	39	.22		.30			
520.0	522.5	75187	2.5	.0	2E48	4.37	.52	2.75	2.80	40.70			8	26	34	.34		.35			
522.5	525.0	75188	2.5	.0	2E89	4.61	.23	1.12	1.56	15.90			9	31	41	.22		.45			
525.0	527.5	75189	2.5	.0	2E1	4.92	.19	.24	.32	19.60			5	35	41	.10		.18			
527.5	530.0	75190	2.5	.0	2E19	4.89	.24	.24	.21	12.40			3	36	40	.57		.11			
530.0	532.5	75191	2.5	.0	2E41	4.52	.15	3.20	4.68	22.70			6	31	37	.57		.17			
532.5	535.0	75192	2.5	.0	2E1	4.32	.15	1.60	1.64	14.60			7	29	37	.34		.22			
535.0	537.5	75193	2.5	.0	2E1	4.22	.15	1.32	1.74	14.00			4	28	33	.34		.11			

DDH: 80-08 UTM-N: 9060.8 UTM-E: 14675.2 UTM-ELEV: 3954.5 TOTAL DEPTH: 601.0 SECTION: 120+000
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	ASSAYS														
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
537.5	540.0	75194	2.5	.0	2F0	4.50	.16	2.70	5.49	15.60				3 25	29	.22		.09			
540.0	542.5	75195	2.5	.0	2F4	4.36	.17	2.94	7.24	14.30				5 25	31	.22		.16			
542.5	545.0	75196	2.5	.0	2F41	4.34	.27	7.39	12.40	18.70				4 22	26	.22		.16			
545.0	547.5	75197	2.5	.0	2E19	4.19	.37	1.97	4.43	10.60				6 26	32	.34		.19			
547.5	550.0	75198	2.5	.0	2E1	4.28	.20	.99	2.90	10.90				3 30	33	.22		.09			
550.0	552.5	75199	2.5	.0	2E41	4.40	.16	1.83	3.87	15.60				3 28	32	.10		.09			
552.5	555.0	75200	2.5	.0	2E41	4.50	.17	2.63	4.17	14.60				2 31	34	.57		.07			
555.0	557.5	75201	2.5	.0	2E41	4.75	.27	2.51	3.95	16.50				1 35	36	.45		.02			
557.5	560.0	75202	2.5	.0	2F0	4.73	.19	2.80	5.17	19.00				1 35	36	.10		.02			
560.0	562.5	75203	2.5	.0	2F0	4.62	.27	2.78	4.46	16.20				1 35	36	.10		.01			
562.5	565.0	75204	2.5	.0	2F4	4.86	.07	3.51	6.69	21.20				1 33	35	.10		.01			
565.0	567.5	75205	2.5	.0	2E41	4.74	.06	6.12	10.20	26.40				2 29	31	.10		.02			
567.5	570.0	75206	2.5	.0	2E41	4.25	.05	3.75	8.24	14.90				2 26	28	.10		.02			
570.0	572.5	75207	2.5	.0	2E48	4.35	.44	2.05	4.46	13.40				3 35	39	.34		.09			
572.5	575.0	75208	2.5	.0	2E48	4.41	.40	1.20	3.99	12.10				5 31	36	.34		.17			
575.0	577.0	75209	2.0	.0	2F9	4.94	.39	1.18	3.91	12.40				5 30	36	.22		.17			
577.0	579.0	75210	2.0	.0	2D30	4.86	.12	2.14	4.13	11.80				1 38	39	.10					
579.0	581.5	75211	2.5	.0	2D43	3.50	.08	3.96	7.56	15.90				1 33	34	.10		.02			
581.5	584.0	75212	2.5	.0	2D43	3.93	.16	4.22	7.59	27.70				15 13	28	.10		.02			
584.0	586.5	75213	2.5	.0	2D9	3.66	.33	1.70	2.39	27.10				9 15	24	.34		.02			
586.5	589.0	75214	2.5	.0	2C0	3.13	.07	.96	2.72	12.80				3 9	13	.81		.04			
589.0	591.5	75215	2.5	.0	2D4	2.98	.10	3.72	5.03	42.90				3 3	7	.81		.03			
591.5	594.0	75216	2.5	.0	2D4	3.28	.06	7.44	10.10	131.30				4 8	13	.45		.08			
594.0	596.5	75217	2.5	.0	2D0	2.89	.06	1.95	5.01	25.50				2 1	4	.57		.03			
596.5	599.0	75218	2.5	.0	2A4	2.92	.04	1.28	4.60	21.50				1 1	3	1.27		.03			
599.0	600.0	75219	1.0	.0	2A4	2.84	.05	1.25	3.16	24.90				1 2	4	1.04		.02			
600.0	601.0	75220	1.0	.0	2A4	2.84	.05	1.25	3.16	24.90				1 2	4	1.04		.02			

DDH: 81-01 UTM-N: 7594.5 UTM-E: 15399.6 UTM-ELEV: 4002.9 TOTAL DEPTH: 320.0 SECTION: 131
RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS----						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
197.0	208.0	75223	11.0	.0	2D0	3.01	.11	4.65	3.90	129.90			3	4	7	.26		.07			
218.0	220.5	75225	2.5	.0	2A4	2.77	.04	1.96	2.47	47.90		.21	1	1	3	.31		.01			
220.5	223.0	75226	2.5	.0	2A0	2.76	.06	.84	2.07	28.60		.27	2	2	4	.34		.01			
223.0	225.5	75227	2.5	.0	2A4	2.95	.11	1.94	4.03	58.20		.41	3	5	9	.23		.04			
225.5	228.0	75228	2.5	.0	2A4	3.07	.11	1.86	4.43	54.40		.14	4	7	11	.32		.03			
228.0	232.2	75229	4.2	.0	2A4	2.92	.16	1.81	4.81	54.40		1.03	3	6	9	.35		.02			
232.2	233.4	75230	1.2	.0	2D0	2.94	.09	2.37	4.34	59.40		1.10	4	3	8	.27		.04			
233.4	238.4	75231	5.0	.0	2A4	2.86	.07	2.00	4.71	64.10		.27	3	3	7	.32		.02			
238.4	243.0	75232	4.6	.0	2A4	2.88	.06	1.82	4.60	56.60		1.17	3	3	6	.34		.02			
243.0	248.0	75233	5.0	.0	2A4	2.67	.04	1.23	2.78	25.20		.27	1	1	3	.37					
248.0	251.6	75234	3.6	.0	2A4	2.58	.05	1.86	2.67	31.40		.41	1	1	3	.36					
251.6	256.6	75235	5.0	.0	2A0	2.82	.10	.46	.65	16.80		.27	3	4	8	.20		.01			
256.6	261.5	75236	4.9	.0	2A4	2.80	.06	2.10	2.33	36.10		.21	2	2	4	.29		.03			
261.5	266.0	75237	4.5	.0	2B0	2.85	.20	.16	.26	6.50		1.17	4	6	11	.20		.06			

DDH: 81-02 UTM-N: 7711.3 UTM-E: 15102.5 UTM-ELEV: 3994.5 TOTAL DEPTH: 400.0 SECTION: 129
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

---DEPTHS---		-----ASSAYS-----																		
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
276.0	277.2	75242	1.2	.0 2AF	3.46	.13	1.29	2.99	20.50		1.03	6	13	20	.10		.12			
277.2	279.0	75243	1.8	.0 2F4	4.36	.08	4.83	6.22	63.40		.34	8	15	24	.07		.23			
279.0	282.0	75244	3.0	.0 2B0	2.92	.13	.52	2.19	12.40		.07	4	4	9	.70		.05			
282.0	284.3	75245	2.3	.0 2E4	4.23	.33	2.79	3.55	44.80		.07	15	15	30	.05		.22			
284.3	287.3	75246	3.0	.0 2F0	4.52	.23	2.38	2.73	23.00		.07	7	21	29	.06		.10			
287.3	290.1	75247	2.8	.0 2F0	4.41	.23	3.33	4.88	36.10		.07	8	20	28	.03		.11			
290.1	293.0	75248	2.9	.0 2A4	3.13	.24	1.98	3.68	39.80		.41	9	6	15	.31		.11			
293.0	296.0	75249	3.0	.0 2C0	2.81	.07	.82	1.89	21.20		.21	2	2	4	.51		.01			
296.0	299.0	75250	3.0	.0 2C0	2.82	.10	.96	2.36	27.40		.07	3	2	6	.52		.01			
299.0	302.0	75251	3.0	.0 2C0	2.79	.09	.96	2.82	30.20		.96	3	2	6	.52		.03			
302.0	306.0	75252	4.0	.0 2C0	2.87	.15	.74	2.67	32.70		.21	3	5	8	.48		.04			
306.0	308.0	75253	2.0	.0 2C0	2.87	.08	.73	1.61	28.90		.07	4	3	8	.53		.05			
308.0	312.0	75254	4.0	.0 2A0	2.88	.08	.96	1.92	27.40		.75	3	3	6	.42		.02			
312.0	316.0	75255	4.0	.0 2A0	2.73	.05	.84	1.87	20.50		.34	2	1	4	.40		.02			
316.0	320.0	75256	4.0	.0 2A0	2.67	.04	.46	1.35	13.10		.17	2	1	4	.37		.02			
320.0	324.5	75257	4.5	.0 2A0	2.79	.10	1.00	1.81	31.70		.07	3	3	7	.32		.05			

DDH: 81-04 UTM-N: 7297.5 UTM-E: 15299.4 UTM-ELEV: 4018.7 TOTAL DEPTH: 305.0 SECTION: 132
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
184.1	185.4	75275	1.3	.0	2F4	4.10	.11	7.89	8.87	150.80		.75	7	16	24	.31		.20			
190.8	192.0	75277	1.2	.0	2D4	3.21	.29	6.07	7.96	126.90		.55	4	7	11	.24		.13			
192.0	194.7	75278	2.7	.0	2F4	4.25	.27	6.86	7.43	130.90		.27	10	17	28	.38		.37			
194.7	195.6	75279	.9	.0	2BC	3.06	.35	2.74	2.52	51.60		.62	5	7	13	2.05		.14			
197.3	200.3	75281	3.0	.0	2DG	3.19	.26	2.81	2.56	50.10		.07	5	6	11	8.58		.16			
200.3	201.6	75282	1.3	.0	2BC	2.84	.04	.57	.97	10.60		.07	2	2	4	8.25		.06			
201.6	204.0	75283	2.4	.0	2L19	2.97	.07	3.48	2.59	98.30		2.47	2	5	7	3.87		.10			
204.0	205.4	75284	1.4	.0	2L19	3.37	.09	7.64	7.34	130.00		.07	6	8	15	.40		.18			
205.4	208.0	75285	2.6	.0	2C0	2.93	.07	.71	1.79	16.20		.07	4	6	10	.92		.03			
208.0	210.5	75286	2.5	.0	2C0	2.73	.03	.82	1.94	17.10		.07	1	2	3	.80		.01			
210.5	214.5	75287	4.0	.0	2C0	2.75	.03	.86	1.48	11.80		.07	1	1	3	2.25		.03			
223.0	226.8	75289	3.8	.0	2EF	4.20	.42	3.72	4.33	56.30		.07	15	18	33	.24		.11			
226.8	228.8	75290	2.0	.0	2F4	4.13	.33	5.74	9.22	81.80		.07	10	16	26	.45		.12			
230.0	235.0	75292	5.0	.0	2A0	2.73	.09	1.79	1.56	32.30		.41	3	3	7	.98		.02			
235.0	241.5	75293	6.5	.0	2A0	2.74	.05	.59	.88	13.70		.34	3	2	6	.56		.05			
241.5	245.2	75294	3.7	.0	2C0	2.81	.06	1.00	1.61	19.90		.48	2	3	6	.90		.02			
245.2	248.2	75295	3.0	.0	2A0	2.98	.11	.95	1.63	24.90		.55	9	4	14	.67		.06			
248.2	251.8	75296	3.6	.0	2A0	3.01	.09	.79	1.52	12.40		.48	5	6	12	.70		.01			
251.8	255.1	75297	3.3	.0	2A0	2.73	.04	.95	1.47	26.40		.07	2	1	3	1.05					
255.1	258.6	75298	3.5	.0	2C0	2.88	.14	1.43	2.11	64.40		.75	3	3	7	.90		.04			
258.6	262.4	75299	3.8	.0	2C0	2.93	.11	2.48	2.82	93.90		.07	4	4	8	.23		.05			
262.4	264.0	75300	1.6	.0	2A0	2.76	.09	.91	1.76	45.10		.27	4	2	6	.88		.04			
264.0	270.2	75301	6.2	.0	2A0	2.78	.13	.56	1.47	24.30		.48	3	3	6	.29		.03			

DDH: 81-05 UTM-N: 7091.8 UTM-E: 15304.1 UTM-ELEV: 4005.8 TOTAL DEPTH: 252.0 SECTION: 133
RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														S.G. W.R.
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	
134.9	138.2	75306	3.3	.0	2D4	3.51	.12	5.76	11.80	64.10		.41	3	11	14	.21		.04			
138.2	140.5	75307	2.3	.0	2F4	4.30	.11	6.83	8.77	265.30		.34	6	19	25	.17		.27			
140.5	144.5	75308	4.0	.0	2D0	2.85	.07	2.29	3.93	49.80		.07	3	2	5	.67		.10			
144.5	146.8	75309	2.3	.0	2B0	2.63	.03	.63	2.28	18.40		.21	1		1	1.12		.01			
146.8	150.0	75310	3.2	.0	2A0	2.69	.03	1.04	2.48	20.80		.07	1		1	1.04		.01			
150.0	153.0	75311	3.0	.0	2A0	2.71	.03	1.52	2.12	45.40		.21	1	1	2	1.08		.01			
153.0	155.5	75312	2.5	.0	2D4	3.24	.06	11.10	6.81	348.30		.34	4	5	9	.17		.07			
155.5	158.0	75313	2.5	.0	2D4	3.02	.06	4.71	6.70	106.90		7.68	5	4	9	.06		.14			
158.0	161.0	75314	3.0	.0	2D0	2.81	.06	1.83	2.56	30.50		.07	3	4	7	.19		.05			
161.0	163.5	75315	2.5	.0	2B0	2.75	.04	.76	1.50	14.30		.48	2	2	4	.46		.04			
163.5	166.0	75316	2.5	.0	2B0	2.82	.05	.99	2.52	19.60		.41	3	3	6	.60		.05			
166.0	168.0	75317	2.0	.0	2C0	3.00	.09	.41	1.16	8.40		.48	4	7	12	.40		.06			
168.0	170.0	75318	2.0	.0	2B0	2.69	.04	.71	1.90	12.40		.07	2	1	4	.82		.02			
170.0	172.0	75319	2.0	.0	2B0	2.73	.06	.41	.30	14.00		.34	3	2	5	.43		.03			
172.0	175.3	75320	3.3	.0	2A0	2.76	.06	.55	.82	13.10		.07	2	2	5	.52		.04			

DDH: 81-07 UTM-N: 7402.5 UTM-E: 15604.1 UTM-ELEV: 4009.8 TOTAL DEPTH: 190.0 SECTION: 133
RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %
53.0	61.0	75342	8.0	.0	2E14	3.76	.14	3.01	5.44	56.30		.07	5	16	21	.49		.10		
61.0	67.5	75343	6.5	.0	2A14	2.98	.06	1.42	4.21	24.90		1.30	4	6	10	.43		.04		
67.5	76.0	75344	8.5	.0	2A1	3.00	.10	1.07	2.78	25.80		1.23	5	6	11	1.11		.04		
76.0	78.0	75345	2.0	.0	2E14	3.44	.13	1.85	5.98	31.70		.07	8	12	20	.39		.06		
78.0	83.0	75346	5.0	.0	2C2	3.38	.13	1.35	1.36	22.70		.34	6	13	20	.55		.04		
83.0	87.7	75347	4.7	.0	2C2	3.13	.08	1.43	1.96	25.50		1.30	5	9	15	.47		.03		
87.7	96.0	75348	8.3	.0	2C0	3.00	.08	.48	1.24	13.70		.62	7	7	14	.62		.08		
96.0	103.0	75349	7.0	.0	2A0	2.80	.06	.64	1.44	16.80		.41	7	3	10	.56		.08		
103.0	106.0	75350	3.0	.0	2A/1D	2.60	.04	.86	1.92	18.70		.55	2	1	3	.34		.02		

DDH: 81-08 UTM-N: 7703.7 UTM-E: 15651.8 UTM-ELEV: 4016.4 TOTAL DEPTH: 288.0 SECTION: 132
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	---ASSAYS---														
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
174.0	176.0	75354	2.0	.0	2D4	3.45	.14	7.73	15.40	8.40		.82	6	6	13	.02		.15			
176.0	178.2	75355	2.2	.0	2D4	3.46	.16	7.22	16.70	67.50		.34	6	7	13	.02		.13			
178.2	180.5	75356	2.3	.0	2C3	3.52	.14	.62	1.47	14.00		.34	7	14	22	.11		.06			
180.5	182.9	75357	2.4	.0	2C3	3.28	.04	.75	.59	13.40		.34	2	14	16	.24		.03			
182.9	186.5	75358	3.6	.0	2D4	3.48	.10	7.34	9.85	113.50		.72	7	7	14	3.71		.17			
186.5	191.0	75359	4.5	.0	1D9	2.90	.05	1.38	1.52	29.90		.34	5	4	9	4.07		.14			
191.0	196.0	75360	5.0	.0	1D9	2.94	.04	1.36	1.60	28.90		.62	6	4	11	3.29		.15			
196.0	198.3	75361	2.3	.0	1D4	2.90	.05	.70	.76	19.00		.62	7	6	13	3.39		.11			
198.3	199.8	75362	1.5	.0	2C3	3.57	.19	1.00	1.11	28.00		.27	11	12	23	5.49		.09			
199.8	201.9	75363	2.1	.0	1D4	2.95	.05	.70	.58	14.90		.34	5	4	9	12.40		.12			
201.9	205.0	75364	3.1	.0	2D4	3.20	.08	3.46	7.48	68.10		.96	6	8	15	2.73		.23			
205.0	209.0	75365	4.0	.0	2D0	3.81	.06	1.63	3.83	33.90		.48	3	4	7	.18		.06			
209.0	213.0	75366	4.0	.0	2D0	2.85	.04	1.63	3.93	30.20		1.03	3	3	6	.40		.04			
213.0	217.0	75367	4.0	.0	2D0	2.90	.05	2.47	2.86	45.40		.34	3	4	7	.13		.03			
217.0	221.0	75368	4.0	.0	2D0	2.91	.05	1.54	3.37	26.10		.75	3	4	8	.36		.04			
221.0	223.4	75369	2.4	.0	2F4	4.33	.12	6.06	9.34	73.70		1.65	7	19	27	.06		.08			
223.4	226.8	75370	3.4	.0	2F4	4.62	.04	7.96	12.10	75.90		.55	1	22	24	.04		.02			
226.8	230.8	75371	4.0	.0	2E0	4.64	.39	1.45	.84	25.80		2.33	5	27	32	.04		.18			
230.8	233.4	75372	2.6	.0	2E0	4.66	.43	.28	.36	14.90		.07	5	29	34	.03		.14			
233.4	235.4	75373	2.0	.0	2E1	4.39	.30	.85	.95	17.70		.07	4	27	31	.03		.15			
235.4	239.0	75374	3.6	.0	2E1	4.21	.16	1.25	1.93	16.80		.07	5	21	26	.03		.24			
239.0	244.1	75375	5.1	.0	2E14	4.44	.21	4.89	7.77	51.00		.07	7	19	26	.03		.21			
244.1	247.0	75376	2.9	.0	2E0	4.08	.23	1.06	2.25	19.30		.34	10	18	28	.04		.29			
247.0	248.3	75377	1.3	.0	2E1	3.96	.50	1.71	2.89	27.10		.14	18	12	30	.06		.09			
248.3	250.0	75378	1.7	.0	2H84	4.39	.12	4.10	7.26	34.20		.07	6	19	25	.04		.18			
250.0	255.5	75379	5.5	.0	2F0	3.15	.11	1.77	6.90	25.20		.27	5	6	12	.29		.10			
255.5	260.5	75380	5.0	.0	2A4	2.91	.03	2.40	6.69	21.20		.07	2	3	5	.31		.03			
260.5	266.7	75381	6.2	.0	2A4	2.92	.04	2.42	4.79	29.90		.69	2	3	6	.24		.03			

DDH: 81-10 UTM-N: 7922.9 UTM-E: 15325.7 UTM-ELEV: 4016.1 TOTAL DEPTH: 538.0 SECTION: 129
RFE: 92 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----		-----ASSAYS-----																		
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
372.0	376.8	75388	4.8	.0 2F4	4.52	.22	4.92	6.09	86.80		1.23	6	22	29	.07		.18			
376.8	378.0	75389	1.2	.0 1D4	3.28	.13	1.10	.52	41.40		.34	19	6	25	.31		.66			
378.0	381.0	75390	3.0	.0 2E7	4.43	.15	.61	.54	19.00		.07	8	25	34	.03		.19			
381.0	383.5	75391	2.5	.0 2F4	4.57	.18	.84	.74	16.20		.17	5	28	33	.04		.14			
383.5	386.0	75392	2.5	.0 ****	4.65	.12	6.21	6.02	83.40		.62	6	23	29	.05		.31			
386.0	388.5	75393	2.5	.0 2F4	4.38	.27	8.57	7.95	97.70		1.03	3	19	23	.05		.13			
388.5	391.0	75394	2.5	.0 2F0	4.56	.28	1.47	1.42	20.80		.07	6	23	29	.02		.29			
391.0	393.0	75395	2.0	.0 2F0	4.29	.27	4.36	5.38	49.50		.34	8	18	27	.02		.76			
393.0	408.0	75396	15.0	.0 2F0	4.52	.19	4.47	5.41	54.40		.07	7	21	28	.01		.42			
408.0	410.5	75397	2.5	.0 2C0	2.95	.18	.19	.55	8.70		.07	4	6	11	.32		.04			
410.5	413.0	75398	2.5	.0 2C0	3.26	.30	.31	1.17	16.50		.51	7	11	19	.10		.05			
413.0	415.5	75399	2.5	.0 2C0	3.34	.21	2.05	1.58	36.70		.07	7	11	19	.07		.06			
415.5	418.4	75400	2.9	.0 2C0	3.07	.17	.69	.30	15.60		.21	7	7	15	.19		.14			
418.4	422.0	75401	3.6	.0 2C0	2.80	.12	1.16	.61	22.10		.34	3	5	8	.40		.05			
422.0	423.6	75402	1.6	.0 2E0	3.43	.19	.38	.12	13.40		.07	6	15	22	.08		.04			
423.6	425.5	75403	1.9	.0 2C2	3.45	.20	.07	.10	14.00		.21	5	15	20	.06		.03			
425.5	427.0	75404	1.5	.0 2E4	3.96	.09	1.99	3.29	22.10		.07	6	19	25	.02		.14			
427.0	429.3	75405	2.3	.0 2E4	4.42	.10	1.88	2.87	22.70		.07	3	25	28	.02		.13			

DDH: 81-11 UTM-N: 7991.9 UTM-E: 15396.3 UTM-ELEV: 4024.9 TOTAL DEPTH: 533.0 SECTION: 129
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	ASSAYS														
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
286.5	288.0	75410	1.5	.0	2J4	4.12	.34	3.80	7.23	84.60		.14	12	16	28	.38		.30			
288.0	290.0	75411	2.0	.0	2H4	3.87	.35	1.92	3.14	41.70		.07	17	13	31	.02		.12			
290.0	292.5	75412	2.5	.0	2H4	4.21	.50	2.42	5.24	56.30			21	12	34	.04		.22			
302.0	304.0	75414	2.0	.0	2L1	3.10	.26	.88	1.13	27.10		.07	6	7	13	.24		.06			
304.0	309.5	75415	5.5	.0	2C7	3.38	.08	.26	1.04	20.20		.07	2	13	15	.17		.05			
309.5	313.0	75416	3.5	.0	2C7	3.53	.04	1.02	2.41	21.80		.14		14	15	.14		.02			
313.0	314.0	75417	1.0	.0	2F4	4.57	.01	3.52	7.87	37.30		.01		23	24	.14		.03			
314.0	318.0	75418	4.0	.0	2E4	4.42	.08	7.32	11.70	67.80		.07		19	19	.58		.04			
318.0	319.7	75419	1.7	.0	2F4	3.85	.11	2.39	11.60	44.50			2	15	18	3.44		.09			
319.7	321.4	75420	1.7	.0	2L4	3.13	.05	5.96	2.84	51.60			2	6	8	11.85		.08			
342.0	346.0	75422	4.0	.0	2E4	4.36	.34	2.04	2.35	47.00			6	26	33	.13		.21			
346.0	348.0	75423	2.0	.0	2E4	4.56	.17	4.76	4.48	74.60		.07	5	24	29	.06		.21			
357.0	359.5	75425	2.5	.0	2E4	3.76	.30	4.93	2.65	76.20		.07	7	16	23	.20		.14			
359.5	362.0	75426	2.5	.0	2E4	4.02	.15	3.32	1.66	64.40		.07	9	18	28	.10		.16			
362.0	365.5	75427	3.5	.0	2E0	4.58	.14	.89	1.15	19.30		.07	7	25	32	.06		.32			
365.5	369.0	75428	3.5	.0	2E0	4.63	.09	.48	.57	22.10		.07	6	28	34	.04		.25			
369.0	372.5	75429	3.5	.0	2E1	4.12	.36	.89	.55	22.40		.07	3	34	38	.04		.08			
372.5	376.0	75430	3.5	.0	2E1	4.08	.59	1.78	1.83	28.30		.07	3	23	26	.05		.07			
376.0	378.5	75431	2.5	.0	2E14	4.48	.17	2.80	1.42	47.90		.07	6	24	31	.03		.12			
378.5	381.0	75432	2.5	.0	2E1	4.54	.09	.88	.53	18.40		.17	1	29	31	.04		.04			
381.0	384.7	75433	3.7	.0	2E0	4.15	.12	1.32	.73	30.20		.07	4	23	27	.06		.14			
384.7	387.6	75434	2.9	.0	2E0	3.75	.22	.53	1.40	31.10		.07	12	17	29	.08		.20			
387.6	390.4	75435	2.8	.0	2H14	3.92	.12	3.72	3.38	53.80		.07	11	16	27	.05		.11			
390.4	392.0	75436	1.6	.0	1D/2H	3.38	.21	1.58	2.68	25.80		.17	12	9	22	.13		.11			
392.0	395.8	75437	3.8	.0	2H4	4.06	.36	4.45	4.09	44.20		.07	12	16	28	.06		.06			
395.8	397.0	75438	1.2	.0	2F0	4.39	.17	4.04	5.30	37.90		.07	7	19	27	.05		.26			
397.0	400.7	75439	3.7	.0	2F4	3.57	.47	3.64	8.00	36.10		.07	5	19	25	.03		.23			
400.7	404.2	75440	3.5	.0	2C2	4.22	.36	.45	1.83	19.00		.07	7	12	20	.06		.11			
404.2	407.7	75441	3.5	.0	2F0	4.13	.26	2.90	4.90	20.20		.07	6	18	24	.03		.19			
407.7	411.2	75442	3.5	.0	2C2	3.95	.20	1.28	2.14	13.10		.07	7	16	24	.04		.37			
411.2	415.3	75443	4.1	.0	2C2	3.93	.29	.58	1.49	13.70		.07	5	18	23	.03		.15			
415.3	418.4	75444	3.1	.0	2E1	3.92	.40	.29	.51	12.10		.07	3	21	24	.07		.08			
418.4	419.9	75445	1.5	.0	2E0	3.31	.14	.44	1.04	7.50		.14	3	13	16	.22		.04			
419.9	423.9	75446	4.0	.0	2F4	4.37	.11	3.50	9.47	23.60		.07	2	23	26	.01		.07			
423.9	427.8	75447	3.9	.0	2F4	4.26	.14	6.45	12.90	36.70		.07	3	19	23	.02		.06			
427.8	429.5	75448	1.7	.0	2F4	4.31	.08	5.05	10.47	29.20		.07	3	19	23	.01		.05			
429.5	433.0	75449	3.5	.0	2F4	3.58	.04	5.02	10.80	35.50		.07	2	13	15	.06		.04			
433.0	437.5	75450	4.5	.0	2F4	3.71	.04	4.84	9.63	37.30		.07	1	16	18	.05		.03			
437.5	438.7	75451	1.2	.0	2F4	4.29	.15	4.05	8.25	26.80		.07	7	21	28	.03		.14			
438.7	440.7	75452	2.0	.0	2F4	4.35	.03	5.68	12.50	39.80		.07	2	21	23	.03		.04			
440.7	442.0	75453	1.3	.0	2D4	3.90	.02	9.70	12.60	47.60		.07	2	15	17	.05		.03			
442.0	445.0	75454	3.0	.0	2F4	4.47	.03	6.18	10.70	33.60		.07	2	23	25	.03		.03			
445.0	448.0	75455	3.0	.0	2F4	3.50	.06	2.82	8.68	25.80		.07	2	14	17	.07		.03			
448.0	451.7	75456	3.7	.0	2FA	3.49	.07	1.64	7.04	23.60		.07	2	15	17	.05		.02			
451.7	456.8	75457	5.1	.0	2FA	3.46	.08	2.14	7.87	24.90		.07	2	14	17	.04		.02			
456.8	460.8	75458	4.0	.0	2FA	3.83	.05	4.30	7.59	31.10		.07	2	18	21	.02		.02			
460.8	463.5	75459	2.7	.0	2FA	3.51	.13	7.79	15.70	55.70		.17	4	8	13	.06		.02			

DDH: 81-12 UTM-N: 7822.6 UTM-E: 15416.8 UTM-ELEV: 4014.7 TOTAL DEPTH: 488.0 SECTION: 130
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	---ASSAYS---													
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %
206.3	208.0	75462	1.7	.0	2C7	3.12	.20	.17	.18	7.80		.07	6	12	18	.10		.04		
208.0	213.2	75463	5.2	.0	2C7	3.18	.28	.37	.62	10.00		.07	7	11	19	2.27		.05		
213.2	214.9	75464	1.7	.0	2F0	4.30	.04	5.60	8.38	52.30		.07	2	26	29	2.34		.05		
218.0	219.6	75466	1.6	.0	2F7	4.32	.12	8.32	7.81	118.50		.17	7	11	19	19.50		.37		
219.6	221.2	75467	1.6	.0	2E7	3.96	.11	8.73	8.38	126.00		.17	5	17	22	3.91		.26		
262.0	264.6	75470	2.6	.0	2H4	4.11	.28	4.20	6.25	50.10		.07	13	20	34	.20		.19		
264.6	267.0	75471	2.4	.0	2E4	4.29	.27	6.22	9.28	80.90		.07	15	19	34	.02		.18		
267.0	277.0	75472	10.0	.0	2E4	4.32	.24	5.50	8.47	73.70		.07	14	21	35	.01		.13		
277.0	278.0	75473	1.0	.0	2F4	4.67	.08	7.86	13.70	81.50		.07	3	27	30	.01		.04		
278.0	282.0	75474	4.0	.0	2E4	4.45	.29	2.50	4.53	35.50		.07	9	29	39	.01		.14		
282.0	287.0	75475	5.0	.0	2E4	4.35	.34	2.71	5.15	37.30		.07	14	25	39	.01		.14		
287.0	292.0	75476	5.0	.0	2D0	3.23	.10	2.15	4.22	32.00		.07	6	10	16	.16		.07		
292.0	299.8	75477	7.8	.0	2D0	3.52	.21	2.32	3.54	34.50		.07	8	16	24	.07		.08		
299.8	301.1	75478	1.3	.0	2E7	3.71	.22	.57	1.86	17.10		.07	9	23	32	.06		.06		
301.1	303.9	75479	2.8	.0	2A4	3.24	.11	1.96	4.67	34.20		.07	7	10	17	.17		.14		
303.9	309.5	75480	5.6	.0	2H1	3.57	.26	1.75	6.28	27.70		.07	7	16	24	.06		.07		
309.5	314.0	75481	4.5	.0	2F4	4.58	.16	5.34	8.67	42.90		.07	4	29	33	.02		.19		
314.0	318.0	75482	4.0	.0	2E1	3.91	.18	1.30	2.32	19.30		.07	4	27	31	.02		.16		
318.0	322.0	75483	4.0	.0	2E1	4.00	.14	.83	2.36	12.10		.07	4	28	33	.01		.18		
322.0	325.0	75484	3.0	.0	2E4	3.94	.17	2.13	2.69	16.80		.07	5	25	30	.06		.15		
325.0	328.0	75485	3.0	.0	2D4	2.98	.11	2.70	7.93	23.60		.07	3	3	6	.23		.03		
328.0	332.5	75486	4.5	.0	2A4	2.96	.07	1.11	4.49	27.40		.48	3	5	9	.24		.01		
332.5	337.0	75487	4.5	.0	2C0	2.94	.09	.94	2.82	23.30		.07	4	5	9	.21		.03		
337.0	342.0	75488	5.0	.0	2D0	2.96	.05	2.79	5.16	27.70		.17	3	4	7	.04		.02		
342.0	347.0	75489	5.0	.0	2D0	2.92	.04	2.45	3.94	25.20		.14	3	3	6	.20		.02		
347.0	350.0	75490	3.0	.0	2C0	2.90	.07	1.59	1.97	16.20		.07	3	4	8	.21		.03		
350.0	354.9	75491	4.9	.0	2D4	3.10	.06	5.97	4.19	67.50		.21	4	5	10	.14		.03		
354.9	360.7	75492	5.8	.0	2D4	3.23	.06	7.90	6.47	65.30		.21	5	5	10	.18		.08		
360.7	362.3	75493	1.6	.0	2D4	3.39	.13	5.11	13.40	54.10		.82	6	7	13	.13		.04		
362.3	366.7	75494	4.4	.0	2A4	2.93	.04	1.90	4.94	21.80		.69	3	3	7	.24		.01		
366.7	370.0	75495	3.3	.0	2D0	2.98	.03	3.02	5.78	31.40		.89	5	3	8	.10		.04		
370.0	374.0	75496	4.0	.0	2D7	3.08	.06	2.52	4.95	29.50		.82	6	6	12	.22		.05		
374.0	379.5	75497	5.5	.0	2D7	3.02	.05	3.43	4.84	39.80		.75	4	5	9	.09		.03		
379.5	385.0	75498	5.5	.0	2E4	3.92	.18	6.74	14.00	79.90		.07	6	17	23	.04		.04		
385.0	390.0	75499	5.0	.0	2A4	3.02	.01	2.05	8.31	19.30		.84	2	5	8	.24		.02		
390.0	394.0	75500	4.0	.0	2A4	2.91	.02	2.54	4.60	19.60		.69	1	4	6	.18		.02		
394.0	396.4	75501	2.4	.0	2A4	2.91	.06	2.27	5.14	20.20		.07	3	11	14	.23		.02		
396.4	400.0	75502	3.6	.0	2D4	3.38	.09	5.67	11.90	35.50		.07	6		6	.08		.03		
400.0	405.0	75503	5.0	.0	2A4	2.84	.02	2.49	5.05	22.10		.34	2	2	5	.25		.02		
405.0	410.0	75504	5.0	.0	2A4	3.19	.10	1.70	4.98	23.60		.27	6	10	16	.08		.03		
410.0	415.0	75505	5.0	.0	2A4	3.27	.10	1.48	3.83	21.80		.07	5	13	19	.06		.03		
415.0	420.0	75506	5.0	.0	2A0	2.98	.12	1.34	1.99	18.40		.07	4	7	11	.14		.02		
420.0	424.1	75507	4.1	.0	2A0	2.99	.09	.82	1.23	15.60		.62	3	5	8	.18		.01		
424.1	428.2	75508	4.1	.0	2C0	3.07	.17	.41	2.78	9.30		.17	7	8	15	.09		.06		
444.9	447.0	75510	2.1	.0	0Q9	3.73	.10	29.90	3.47	344.60		.96	3	3	6	.08		.05		
447.0	452.4	75511	5.4	.0	2D7	3.27	.39	3.89	4.68	41.10		.07	4	12	16	.09		.02		

DDH: 81-13 UTM-N: 7898.9 UTM-E: 15112.8 UTM-ELEV: 4014.1 TOTAL DEPTH: 504.0 SECTION: 128
RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
330.9	336.2	75515	5.3	.0	2E4	4.33	.24	7.18	8.17	97.70		.07	13	21	34	.04		.17			
336.2	340.0	75516	3.8	.0	2E0	4.71	.11	2.24	1.67	24.60		.07	4	37	42	.01		.10			
340.0	344.8	75517	4.8	.0	2E4	4.72	.24	2.80	2.60	27.10		.07	4	34	39			.10			
344.8	348.0	75518	3.2	.0	2F4	4.65	.21	4.29	6.08	32.70		.07	4	33	38	.01		.06			
348.0	351.0	75519	3.0	.0	2F4	4.75	.15	5.04	5.89	37.00		.07	2	36	38	.02		.04			
351.0	356.0	75520	5.0	.0	2E4	4.66	.08	3.48	3.99	35.50		.07	3	35	38	.08		.06			
356.0	358.0	75521	2.0	.0	2JF	4.21	.17	2.50	6.15	38.30		.07	7	26	34	.09		.12			
358.0	360.0	75522	2.0	.0	2AC	3.00	.12	.97	1.85	24.30		.07	5	6	11	.31		.08			
360.0	364.0	75523	4.0	.0	2A0	2.80	.09	.93	2.15	20.80		.07	2	3	6	.27		.02			
364.0	369.0	75524	5.0	.0	2A4	2.72	.04	1.35	3.26	16.80		.07	1	1	3	2.01		.03			
417.0	423.0	75527	6.0	.0	2A4	3.09	.12	2.34	4.25	51.00		.41	5	6	12	.20		.04			
423.0	425.4	75528	2.4	.0	2A3	3.03	.10	.77	2.63	28.90		.82	5	7	12	.22		.03			
425.4	428.0	75529	2.6	.0	2A0	2.85	.05	1.15	2.26	21.10		.07	3	3	7	.22		.03			
428.0	434.0	75530	6.0	.0	2A0	2.71	.06	1.34	1.97	14.60		.07	1	2	3	.23		.01			
434.0	440.0	75531	6.0	.0	2A4	2.81	.09	2.84	3.88	26.10		.07	2		2	.13		.02			
440.0	445.0	75532	5.0	.0	2A4	2.91	.12	2.03	4.22	30.80		.07	3	2	6	.11		.02			
445.0	450.0	75533	5.0	.0	2A4	2.79	.09	1.62	3.57	23.00		.14	3	3	6	.14		.03			

DDH: 81-14 UTM-N: 8095.1 UTM-E: 15301.6 UTM-ELEV: 4050.0 TOTAL DEPTH: 641.0 SECTION: 128
 RFE: S2 RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
336.7	341.0	75538	4.3	.0	2C0	2.80	.10	.18	.13	8.40		.07	3	4	8	.36		.03			
341.0	346.0	75539	5.0	.0	2C0	2.86	.10	.13	.07	7.50		.07	4	6	10	.17		.03			
346.0	351.0	75540	5.0	.0	2C0	3.03	.19	.10	.29	10.00		.07	5	10	15	.14		.05			
351.0	356.0	75541	5.0	.0	2C0	3.11	.24	.22	.19	16.50		.07	4	12	17	.07		.05			
356.0	361.0	75542	5.0	.0	2C0	3.23	.27	.17	1.17	19.60		.07	5	14	20	.05		.12			
361.0	367.2	75543	6.2	.0	2C3	3.18	.17	.10	.44	11.20		.07	4	14	18	.09		.04			
367.2	370.5	75544	3.3	.0	2A3	3.30	.13	.08	.22	8.10		.07	3	18	22	.05		.02			
370.5	373.5	75545	3.0	.0	2F4	3.63	.10	1.98	10.70	30.80		.07	3	17	21	.03		.07			
373.5	376.0	75546	2.5	.0	2F4	3.59	.04	4.43	9.50	52.30		.17	3	16	19	.09		.03			
376.0	379.3	75547	3.3	.0	2E1	3.75	.03	.37	2.32	12.80		.07	2	27	29	.11		.03			
379.3	382.3	75548	3.0	.0	2F4	3.82	.04	3.27	7.80	35.80		.07	2	24	26	.07		.01			
383.1	388.2	75550	5.1	.0	2C3	3.73	.09	.09	.06	8.70		.27	1	28	29	.07		.01			
389.5	392.5	75552	3.0	.0	2C3	3.70	.14	.58	2.55	13.10		.41		27	27	.10		.01			
392.5	395.0	75553	2.5	.0	2F4	4.31	.05	5.33	8.63	62.20		.14	1	28	30	3.98		.05			
414.0	417.0	75555	3.0	.0	2F0	4.43	.12	3.96	2.37	110.40		.21	6	31	38	.17		.25			
434.6	435.9	75558	1.3	.0	2F0	4.16	.35	1.68	2.40	32.70		.27	5	29	35	2.10		.08			
435.9	440.0	75559	4.1	.0	2G4	4.59	.05	6.57	9.14	92.40		.07	2	12	15	33.80		.05			
440.0	445.0	75560	5.0	.0	2G4	4.51	.06	5.51	8.26	76.20		.07	2	14	16	32.95		.07			
445.0	450.0	75561	5.0	.0	2G4	4.43	.06	6.26	10.19	89.30		.07	2	9	11	38.26		.05			
450.0	454.0	75562	4.0	.0	2G4	4.52	.05	6.08	9.28	90.20		.07	1	9	11	44.12		.03			
454.0	457.0	75563	3.0	.0	2G4	4.46	.04	5.64	9.24	92.70		.07	1	8	10	42.69		.03			
457.0	460.0	75564	3.0	.0	2J7	3.97	.29	2.85	1.80	53.80		.07	11	24	35	2.01		.17			
465.5	467.8	75566	2.3	.0	2E0	4.40	.21	.84	1.00	40.40		.07	9	31	41	2.80		.13			
470.0	474.4	75568	4.4	.0	2H9	4.08	.29	.35	1.40	25.20		.07	26	17	44	.04		.04			
474.4	479.3	75569	4.9	.0	2H4	4.28	.32	3.47	7.32	53.80		.48	28	13	41	.07		.06			
479.3	482.3	75570	3.0	.0	2E7	3.65	.22	.08	.82	12.40		.17	10	28	39	.03		.07			
482.3	485.0	75571	2.7	.0	2H9	4.03	.22	.58	2.10	23.90		.41	26	16	42	.03		.04			
485.0	488.0	75572	3.0	.0	2C7	3.59	.08	.09	.15	6.80		.21	5	23	29	.03		.03			
488.0	491.2	75573	3.2	.0	2C7	3.38	.14	.09	.27	10.00		.27	15	12	28	.02		.02			
491.2	496.2	75574	5.0	.0	2H9	4.05	.20	1.06	3.28	24.30		.14	34	8	43	.02		.02			
496.2	500.2	75575	4.0	.0	2D3	3.72	.15	1.76	2.80	28.60		.27	8	21	29	.06		.11			
500.2	504.5	75576	4.3	.0	2C3	3.51	.35	1.29	1.04	31.70		.07	5	20	26	.03		.09			
504.5	508.0	75577	3.5	.0	2H9	3.96	.32	1.44	3.55	34.50		.07	27	11	39	.02		.06			
508.0	511.0	75578	3.0	.0	2C3	3.83	.32	.69	.83	16.20		.07	4	27	31	.03		.14			
511.0	516.0	75579	5.0	.0	2C3	3.65	.27	.05	.57	13.40		.24	2	26	28	.04		.03			
516.0	521.0	75580	5.0	.0	2C3	3.81	.26	.06	.49	7.80		.07	1	29	30	.05		.03			
521.0	525.0	75581	4.0	.0	2C3	3.89	.22	.89	1.82	13.70		.07	3	27	31	.05		.13			
525.0	528.0	75582	3.0	.0	2C3	3.65	.22	.10	.54	10.00		.07	2	26	28	.05		.04			
528.0	532.0	75583	4.0	.0	2F4	4.04	.10	4.31	9.83	27.10		.07	3	24	28	.20		.08			
532.0	536.0	75584	4.0	.0	2F4	4.52	.03	5.82	11.20	37.00		.07	2	30	32	.05		.03			
536.0	540.0	75585	4.0	.0	2F4	4.37	.06	7.17	13.90	33.30		.07	3	26	29	.04		.04			
540.0	543.4	75586	3.4	.0	2F4	4.59	.01	6.29	12.50	35.50		.14	1	30	32	.04		.02			
543.4	544.4	75587	1.0	.0	2F4	3.68	.01	3.95	13.00	24.30		.07	1	18	19	.15		.01			
544.4	549.0	75588	4.6	.0	2F4	4.50	.03	7.48	15.50	39.50		.41	2	26	29	.05		.03			
549.0	554.0	75589	5.0	.0	2F4	4.39	.04	7.13	13.50	39.80		.07	2	26	29	.04		.02			

DDH: 81-14 UTM-N: 8095.1 UTM-E: 15301.6 UTM-ELEV: 4050.0 TOTAL DEPTH: 641.0 SECTION: 128
RFE: S2 RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----							-----ASSAYS-----													
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
554.0	559.0	75590	5.0	.0 2D3	3.40	.06	.57	3.61	10.00		.07	2	26	29	.11		.03			
559.0	564.0	75591	5.0	.0 2A3	3.52	.02	.46	1.69	13.10		.07	1	21	23	.10		.02			
564.0	569.0	75592	5.0	.0 2A3	3.39	.03	.06	.35	3.70		.07	1	21	22	.10		.01			
569.0	572.4	75593	3.4	.0 2A34	3.41	.26	2.43	6.34	26.10		.51	5	15	20	.06		.05			

DDH: 81-15 UTM-N: 8084.3 UTM-E: 15504.8 UTM-ELEV: 4100.8 TOTAL DEPTH: 685.0 SECTION: 129
RFE: S2 RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS----							-----ASSAYS-----													
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
477.5	482.0	75598	4.5	.0 2D0	3.95	.08	5.33	8.69	50.70		.41	3	22	25	.70		.05			
482.0	485.7	75599	3.7	.0 2D0	3.72	.03	2.60	6.75	26.40		.27	1	21	23	.91		.02			
485.7	488.0	75600	2.3	.0 2CE	3.74	.06	2.02	2.81	34.80		.48	4	19	23	5.33		.10			
488.0	491.4	75601	3.4	.0 2CE4	3.37	.12	1.76	1.98	25.80		.62	6	15	21	.22		.14			
493.2	497.0	75603	3.8	.0 2CE4	3.65	.12	2.34	3.53	44.50		1.20	3	16	19	8.71		.10			
497.0	500.7	75604	3.7	.0 2CE	3.22	.17	1.01	1.00	20.80		1.23	3	14	18	.29		.06			
500.7	503.7	75605	3.0	.0 2EF	3.76	.15	2.75	3.78	27.70		.07		19	19	.07		.18			
503.7	506.6	75606	2.9	.0 2EF	3.91	.14	4.92	6.85	41.10		.17	8	20	29	.06		.12			
506.6	510.0	75607	3.4	.0 2DE	3.43	.11	3.63	6.45	40.70		.27	8	13	21	.20		.11			
510.0	516.0	75608	6.0	.0 2CE	3.33	.16	.60	3.18	16.20		.51	6	16	23	.23		.08			
516.0	521.0	75609	5.0	.0 2DE	3.96	.26	2.40	3.21	30.50		.07	5	25	31	.01		.19			
521.0	526.0	75610	5.0	.0 2DE	4.29	.25	4.00	4.94	35.10		.07	6	28	34	.01		.25			
526.0	530.0	75611	4.0	.0 2CE	3.64	.23	.45	1.08	12.80		.07	4	23	28	.01		.18			
530.0	533.0	75612	3.0	.0 2CE	3.46	.22	.98	2.17	10.90		.17	5	19	24	.04		.16			
533.0	534.0	75613	1.0	.0 1D9	3.47	.07	.95	3.11	19.30		.07	2	19	21	.08		.06			
534.0	537.0	75614	3.0	.0 2E1	3.87	.18	.69	1.73	10.30		.17	3	27	31	.02		.11			
537.0	540.0	75615	3.0	.0 2E1	4.05	.33	.41	1.69	13.10		.27	5	29	34	.01		.17			
540.0	542.0	75616	2.0	.0 2C9	3.50	.43	.80	1.75	13.40		.27	4	21	25	.01		.10			
542.0	545.3	75617	3.3	.0 2EF	4.27	.09	4.20	8.49	19.00		.14	4	28	32	.01		.08			
545.3	547.7	75618	2.4	.0 2EF	4.18	.05	4.95	12.00	18.00		.07	3	24	27	.06		.04			
547.7	552.0	75619	4.3	.0 2EF	3.49	.08	5.54	10.70	33.00		.07	3	12	15	.06		.04			
552.0	555.6	75620	3.6	.0 2F4	4.59	.02	6.72	10.40	30.20		.07	2	31	33	.03		.02			

DDH: 81-16 UTM-N: 7843.8 UTM-E: 15662.7 UTM-ELEV: 4013.1 TOTAL DEPTH: 518.0 SECTION: 131
 RFE: S2 RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	ASSAYS															S.G. W.R.
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %		
218.7	220.6	75626	1.9	.0	2D4	3.30	.53	5.72	4.59	235.10		.31	5	9	15	.70		.10				
220.6	222.5	75627	1.9	.0	2E4	3.70	.57	1.50	4.57	65.90		.17	9	19	29	.63		.10				
222.5	224.6	75628	2.1	.0	2D0	3.73	.15	1.09	4.35	33.30		.62	2	23	26	.07		.04				
224.6	226.7	75629	2.1	.0	2D4	3.71	.13	3.64	8.59	74.30		.41	4	19	23	.16		.15				
226.7	228.8	75630	2.1	.0	2D0	3.60	.09	1.65	4.52	38.60		.07	1	22	24	.03		.06				
228.8	231.3	75631	2.5	.0	2E4	3.86	.21	8.33	12.40	84.60		1.10	8	13	22	.07		.39				
231.3	233.4	75632	2.1	.0	2D0	3.72	.19	2.10	6.32	32.00		.41	3	21	25	.04		.13				
233.4	234.5	75633	1.1	.0	2F0	3.85	.04	2.36	5.69	32.70		.62	1	25	26	.02		.01				
234.5	236.9	75634	2.4	.0	2D0	3.76	.04	1.65	6.47	23.90		.17	1	24	25	.01		.02				
236.9	239.3	75635	2.4	.0	2D0	3.76	.07	3.39	5.99	63.10		.27	1	23	24	.06		.03				
239.3	243.5	75636	4.2	.0	2EF/4	4.38	.17	7.56	5.58	163.60		.96	2	29	32	.03		.15				
252.6	253.3	75638	.7	.0	2E0	3.98	.27	.17	.38	13.70		.41	5	29	34	.42		.16				
254.8	257.3	75640	2.5	.0	2E8	4.54	.20	1.03	.30	33.60		.07	6	34	41	.04		.32				
257.3	259.8	75641	2.5	.0	2E8	4.45	.23	.69	.32	29.50		.07	5	35	41	.04		.20				
259.8	262.3	75642	2.5	.0	2E8	4.40	.16	1.02	.36	30.80		.07	5	34	40	.04		.27				
262.3	264.8	75643	2.5	.0	2E8	4.56	.22	1.34	.88	48.50		.14	5	35	40	.02		.34				
264.8	267.3	75644	2.5	.0	2E84	4.59	.27	2.99	2.41	84.30		.17	6	34	40	.06		.39				
267.3	269.8	75645	2.5	.0	2E8	4.52	.14	2.39	1.45	55.10		.17	6	34	40	.04		.36				
269.8	272.3	75646	2.5	.0	2E8	4.45	.10	.05	.17	8.40		.07	5	35	41	.07		.22				
272.3	274.8	75647	2.5	.0	2E8	4.42	.10	.04	.15	6.20		.07	6	35	41	.05		.25				
274.8	277.3	75648	2.5	.0	2E8	4.43	.23	1.21	.20	35.50		.07	5	34	40	.07		.36				
277.3	279.4	75649	2.1	.0	2H9	4.15	.77	.61	.15	22.10		.07	48	4	52	.07		.20				
279.4	281.4	75650	2.0	.0	2H4	4.33	.77	3.10	2.89	85.80		.07	2	5	8	.06		.35				
281.4	283.4	75651	2.0	.0	2C2	4.31	.25	.24	.16	13.40		.17	4	40	44	.07		.20				
283.4	286.2	75652	2.8	.0	2E8	4.43	.16	.14	.22	17.40		.07	3	36	40	.08		.20				
286.2	289.0	75653	2.8	.0	2E84	4.56	.20	3.17	2.67	52.60		.17	6	33	39	.01		.39				
289.0	291.8	75654	2.8	.0	2E8	4.50	.28	.80	.29	63.40		.10	7	34	41	.02		.38				
291.8	294.5	75655	2.7	.0	2E8	4.48	.13	1.58	1.17	70.30		.07	5	34	39	.02		.36				
294.5	296.7	75656	2.2	.0	2F4	4.45	.36	8.15	5.82	143.40		.82	6	27	33	.18		.36				
296.7	298.9	75657	2.2	.0	2F4	4.55	.34	7.51	5.35	143.10		.62	3	31	35	.11		.24				
298.9	300.7	75658	1.8	.0	2E0	4.62	.33	1.68	1.50	50.40		.07	6	34	41	.01		.39				
300.7	301.9	75659	1.2	.0	2F4	4.48	.32	7.35	9.35	121.00		.55	9	23	32	.03		1.19				
301.9	304.1	75660	2.2	.0	2E4	4.44	.30	3.50	1.95	94.20		.69	6	31	38	.01		.51				
304.1	307.6	75661	3.5	.0	2F0	4.50	.16	4.96	2.08	76.80		1.20	4	32	36	.04		.24				
307.6	310.4	75662	2.8	.0	2E4	4.42	.32	4.30	2.28	64.10		1.51	1	34	35	.03		.03				
310.4	313.2	75663	2.8	.0	2E4	4.23	.06	3.26	1.63	87.40		.55	1	30	32	.03		.06				
313.2	315.9	75664	2.7	.0	2E0	3.69	.15	1.56	1.64	87.40		.17	1	24	26	.07		.04				
315.9	318.2	75665	2.3	.0	1D0	3.08	.08	.75	.75	83.00		.33	2	10	13	.21		.06				
318.2	320.6	75666	2.4	.0	2E4	4.07	.28	1.68	2.81	69.00		.17	4	28	32	.03		.20				
320.6	323.0	75667	2.4	.0	2E4	4.23	.30	2.01	2.12	66.90		.07	4	30	35	.01		.20				
323.0	326.1	75668	3.1	.0	2E0	3.86	.28	.62	.63	28.30		.51	3	27	31	.13		.17				
326.1	329.2	75669	3.1	.0	2E0	3.72	.24	.76	1.56	34.20		.27	3	23	26	.09		.16				
329.2	332.0	75670	2.8	.0	2E4	3.49	.18	1.16	3.30	32.00		.07	2	19	21	.09		.18				
332.0	334.8	75671	2.8	.0	2E4	3.57	.15	1.46	3.25	33.00		.07	3	18	22	.10		.11				
334.8	337.5	75672	2.7	.0	2E4	3.99	.12	2.42	5.57	28.60		.07	4	26	30	.07		.11				

DDH: 81-18 UTM-N: 7845.7 UTM-E: 15256.9 UTM-ELEV: 4012.4 TOTAL DEPTH: 478.0 SECTION: 129
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----						-----ASSAYS-----																
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.	
226.0	229.6	75687	3.6	.0	2C0	3.31	.17	.07	.14	.90		.34	2	18	21	.03		.02				
229.6	230.8	75688	1.2	.0	2E0	2.94	.22	.01	.09	.60		.07	3	30	33	.02		.04				
230.8	234.0	75689	3.2	.0	2C0	3.22	.09	.03	.07	5.60		.17	2	16	19	.07		.03				
234.0	237.2	75690	3.2	.0	2C0	3.63	.09	.09	.42	.30		.07	3	24	28	.06		.05				
237.2	241.0	75691	3.8	.0	2A4F	3.24	.09	.84	10.06	8.70		.07	2	11	14	.09		.04				
241.0	246.0	75692	5.0	.0	2A4F	3.33	.08	1.87	5.70	8.70		.48	2	15	17	.06		.02				
246.0	251.0	75693	5.0	.0	2A4F	3.35	.12	1.59	3.70	13.10		.69	2	16	18	.10		.02				
251.0	252.8	75694	1.8	.0	2F4	4.26	.15	5.65	7.57	79.30		.41	6	16	22	13.86		.28				
252.8	255.0	75695	2.2	.0	2F4	4.57	.20	6.54	5.63	107.60		.82	6	22	29	9.92		.45				
255.0	258.6	75696	3.6	.0	2F4	4.60	.13	6.43	5.85	102.00		.69	6	23	29	10.14		.51				
258.6	259.0	75697	.4	.0	2H0	4.25	.45	1.31	6.11	112.60		.96	12	20	32	2.16		.73				
286.5	288.5	75699	2.0	.0	2D0	3.29	.18	3.84	4.19	74.30		.27	6	8	15	5.17		.25				
288.5	293.0	75700	4.5	.0	2H4	4.21	.33	4.49	7.08	78.10		.17	15	20	35	.37		.25				
293.0	297.0	75701	4.0	.0	2E0	4.70	.16	1.19	1.87	17.40		.07	4	37	42	.07		.07				
297.0	300.0	75702	3.0	.0	2E0	4.82	.03	2.80	3.81	33.60		.07	1	38	39	2.27		.02				
300.0	304.2	75703	4.2	.0	2E0	4.73	.09	1.32	1.48	19.90		.07	3	40	43	.05		.05				
304.2	308.4	75704	4.2	.0	2EF	4.73	.13	3.10	4.98	36.40		.07	3	37	40	.06		.06				
308.4	309.9	75705	1.5	.0	2F4	4.82	.08	4.68	7.34	42.30		.07	1	35	37	.12		.04				
309.9	311.7	75706	1.8	.0	2E4	4.83	.15	2.41	3.57	22.70		.07		40	41	.17		.01				
311.7	314.0	75707	2.3	.0	2F0	4.87	.12	4.24	5.00	43.20		.07	1	38	39	.25		.02				
314.0	318.5	75708	4.5	.0	2H4	4.25	.41	2.98	5.05	38.60		.07	19	21	40	.09		.14				
318.5	321.3	75709	2.8	.0	2EF4	4.61	.26	5.21	8.20	64.10		.07	5	30	36	.45		.11				
321.3	323.4	75710	2.1	.0	2E8	4.50	.39	.89	1.69	17.70		.07	7	34	42	.10		.18				
323.9	326.9	75712	3.0	.0	2E8	4.56	.45	1.08	2.68	20.20		.07	5	36	41	.06		.12				
326.9	329.0	75713	2.1	.0	2E84	4.55	.24	.93	3.75	14.30		.07	6	34	41	.05		.16				
329.0	331.4	75714	2.4	.0	2H4	4.27	.57	3.99	5.64	41.10		.07	20	9	30	.09		.08				
331.4	335.0	75715	3.6	.0	2J7	3.86	.58	2.57	5.14	28.00		.07	13	26	40	.06		.10				
335.0	339.0	75716	4.0	.0	2D0	3.26	.16	1.40	4.23	24.30		.07	6	6	12	.20		.06				
339.0	343.0	75717	4.0	.0	2C0	2.94	.15	1.14	2.85	25.50		.07	6	2	8	.57		.07				
343.0	348.0	75718	5.0	.0	2D0	2.71	.03	1.34	2.93	26.10		.07	1	1	3	.24		.03				
348.0	351.0	75719	3.0	.0	2D0	2.82	.04	4.00	2.22	74.30		.17	1	1	3	.22		.04				
351.0	354.3	75720	3.3	.0	2C0	2.74	.05	.95	2.13	24.30		.41	1	1	3	.24		.03				
354.3	359.0	75721	4.7	.0	2D0	2.62	.04	1.21	2.79	28.90		.27	1	1	3	.22		.03				
359.0	364.0	75722	5.0	.0	2A4	2.63	.03	1.36	2.84	22.70		.17	1	1	2	.26		.02				
364.0	369.5	75723	5.5	.0	2A0	2.70	.04	.88	1.90	16.80		.14	2	1	3	.40		.03				
369.5	372.2	75724	2.7	.0	2A0	2.67	.04	.88	1.73	15.20		.17	2	2	4	.36		.04				
372.2	377.0	75725	4.8	.0	2A0	2.72	3.11	1.09	1.63	24.90		.17	2	2	5	.25		.04				
377.0	381.0	75726	4.0	.0	2A0	2.82	.18	.85	.65	46.00		.27	3	4	8	.18		.04				
381.0	384.0	75727	3.0	.0	2A0	2.97	.26	.42	.39	30.20		.07	4	6	10	.11		.04				
384.0	388.0	75728	4.0	.0	2A4	2.96	.08	1.73	4.36	28.60		.07	2	5	7	.31		.03				
388.0	393.7	75729	5.7	.0	2A4	2.94	.08	2.26	2.61	25.80		.48	1	5	7	.26		.03				
393.7	398.7	75730	5.0	.0	2A0	2.73	.04	1.10	2.82	20.20		.07	1	2	3	.43		.03				
398.7	402.0	75731	3.3	.0	2A0	2.84	.03	1.14	3.53	20.50		.62	1	3	4	.17		.03				
402.0	406.0	75732	4.0	.0	2A4	2.71	.04	1.68	3.08	19.30		.17	1	2	3	.19		.03				
406.0	408.9	75733	2.9	.0	2D0	2.86	.06	1.25	3.87	21.50		.96	2	3	5	.23		.03				
408.9	414.0	75734	5.1	.0	2A4	2.66	.03	1.36	3.40	17.70		.48	1	1	2	.16		.02				
414.0	419.0	75735	5.0	.0	2A4	2.73	.02	1.51	3.19	18.00		.27				.18		.01				
419.0	424.0	75736	5.0	.0	2A4	2.72	.02	1.73	3.92	27.40		.75	1		1	.16		.02				
424.0	428.0	75737	4.0	.0	2A4	2.72	.04	1.35	3.21	26.40		.96	1	1	3	.23		.03				

DDH: 81-18 UTM-N: 7845.7 UTM-E: 15256.9 UTM-ELEV: 4012.4 TOTAL DEPTH: 478.0 SECTION: 129
RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----				-----ASSAYS-----																
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
428.0	430.0	75738	2.0	.0 2D0	2.85	.08	1.38	4.92	30.20		.55	2	1	4	.19		.04			

DDH: 81-19 UTM-N: 8102.2 UTM-E: 15699.7 UTM-ELEV: 4101.3 TOTAL DEPTH: 624.0 SECTION: 130
RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

---DEPTHS---		SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	ASSAYS														
FROM	TO					Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
396.0	398.7	75744	2.7	.0 2D0	4.15	.18	3.91	5.58	41.10		.17	5	27	33	.18		.08			
398.7	401.4	75745	2.7	.0 2D4	4.14	.18	1.97	19.51	24.60		.07	7	29	37	.04		.28			
401.4	403.7	75746	2.3	.0 2E82	4.42	.13	.92	2.48	17.10		.07	8	32	41	.04		.54			
403.7	406.0	75747	2.3	.0 2E84	4.58	.08	2.33	3.55	21.80		.07	6	34	41	.04		.35			
406.0	412.0	75748	6.0	.0 2F84	4.50	.33	5.15	7.04	62.50		.07	6	29	36	.03		.44			
412.0	414.4	75749	2.4	.0 2D0	4.11	.19	3.36	3.54	60.30		.82	1	30	32	.03		.05			
414.4	416.9	75750	2.5	.0 2C0	3.64	.80	2.41	.51	89.90		1.37	1	24	25	.03		.02			
416.9	419.7	75751	2.8	.0 2FE4	4.65	.20	5.64	5.07	74.60		.41	2	34	37	.03		.04			
419.7	422.1	75752	2.4	.0 2D0	3.98	.11	3.86	6.14	36.70		.27	1	26	27	.03		.02			
422.1	424.5	75753	2.4	.0 2D0	4.13	.34	2.74	4.76	37.60		.51	1	31	32	.05		.02			
424.5	426.9	75754	2.4	.0 2D0	4.19	.13	2.27	5.94	28.00		.69	1	30	31	.03		.02			
426.9	429.3	75755	2.4	.0 2D0	4.00	.10	3.55	2.82	44.50		1.20	1	28	29	.05		.01			
429.3	431.7	75756	2.4	.0 2D0	4.24	.06	2.58	5.20	33.00		.69	1	31	33	.06		.01			
431.7	434.1	75757	2.4	.0 2D0	4.11	.07	2.49	4.27	26.70		.34	1	30	31	.05		.01			
434.1	436.6	75758	2.5	.0 2C0	3.67	.19	.47	1.39	12.40		.48		26	27	.06		.01			
436.6	439.1	75759	2.5	.0 2D0	3.81	.09	2.48	3.56	24.90		.27		26	27	.06		.01			
439.1	441.8	75760	2.7	.0 2DE4	4.18	.09	6.42	10.12	67.80		.69	2	25	27	.03		.08			
441.8	444.5	75761	2.7	.0 2DE4	4.44	.02	7.68	12.10	63.80		.17	2	26	29	.03		.09			
444.5	447.0	75762	2.5	.0 2D0	3.63	.20	1.91	2.64	20.80		.34	2	22	25	.04		.15			
447.0	449.4	75763	2.4	.0 2C0	3.61	.17	1.26	2.19	23.00		.51	3	22	26	.06		.12			
449.4	451.5	75764	2.1	.0 2D0	3.53	.40	2.65	2.81	34.20		.69	4	19	23	.05		.13			
451.5	453.3	75765	1.8	.0 2E1	4.43	.06	.27	.52	4.70		.86	2	38	40	.05		.03			
453.3	456.0	75766	2.7	.0 2C0	3.89	.08	1.29	1.84	16.80		.55	1	28	30	.05		.03			
456.0	458.7	75767	2.7	.0 2C0	3.92	.10	.25	1.11	3.10		.07	1	30	32	.03		.02			
458.7	461.4	75768	2.7	.0 2D4	4.41	.15	7.60	4.38	44.50		.07	2	30	32	.03		.07			
461.4	464.2	75769	2.8	.0 2D0	4.08	.26	3.42	1.39	28.30		.07	1	31	33	.01		.06			
464.2	465.2	75770	1.0	.0 2D4	3.95	.41	6.43	5.42	46.70		.07	10	17	28	.02		.58			
465.2	467.8	75771	2.6	.0 2D0	4.07	.18	3.85	3.50	29.20		.07	2	29	31	.02		.13			
467.8	470.4	75772	2.6	.0 2C0	4.12	.31	1.70	1.25	14.30		.07	1	32	33	.02		.06			
470.4	473.0	75773	2.6	.0 2C0	4.02	.24	.09	.55	7.50		.07	1	32	33	.01		.03			
473.0	475.6	75774	2.6	.0 2C0	4.41	.21	.07	.42	5.90		.07	1	39	40	.01		.04			
475.6	478.3	75775	2.7	.0 2C0	4.21	.20	.05	.40	2.80		.07	2	34	36	.02		.09			
478.3	481.0	75776	2.7	.0 2D0	4.13	.27	2.02	2.00	18.70		.07	2	32	34	.01		.08			
481.0	484.0	75777	3.0	.0 2D2	4.00	.23	2.31	2.85	21.80		.07	4	27	32	.02		.15			
484.8	486.3	75779	1.5	.0 2E8	4.41	.47	1.97	2.13	21.80		.07	6	33	39	.02		.27			
486.3	487.5	75780	1.2	.0 2F4	4.41	.19	10.24	9.42	67.50		.07	6	23	29	.03		.43			
487.5	490.2	75781	2.7	.0 2D8	4.17	.22	1.07	3.15	9.00		.07	5	29	35	.01		.24			
490.2	492.8	75782	2.6	.0 2C8	4.03	.28	1.18	1.98	12.80		.07	5	27	33	.02		.22			
492.8	495.4	75783	2.6	.0 2C8	4.07	.22	.13	.72	5.30		.07	5	30	36	.03		.20			
495.4	498.0	75784	2.6	.0 2C8	4.01	.33	.78	1.22	15.90		.07	4	29	34	.03		.18			
498.0	500.7	75785	2.7	.0 2D0	3.85	.22	2.25	3.60	14.00		.07	4	24	28	.01		.32			
500.7	503.4	75786	2.7	.0 2D0	3.69	.12	2.24	5.54	14.60		.07	2	22	24	.10		.04			
503.4	506.1	75787	2.7	.0 2C0	3.51	.18	.50	3.10	18.40		.07	2	21	23	.05		.13			
506.1	508.8	75788	2.7	.0 2C0	3.81	.25	.37	.75	8.70		.07	2	28	30	.02		.13			
508.8	511.5	75789	2.7	.0 2C0	3.74	.19	.03	.76	7.50		.07	1	27	29	.03		.09			
511.5	513.6	75790	2.1	.0 2C3	3.66	.20	.08	.32	2.80		.07	1	27	28	.05		.02			
513.6	515.8	75791	2.2	.0 2C3	3.71	.38	.15	.66	10.90		.07	1	26	28	.04		.06			
515.8	518.0	75792	2.2	.0 2C3	3.20	.51	.94	1.96	12.40		.07	1	33	35	.02		.05			
518.0	520.2	75793	2.2	.0 2C3	4.24	.29	.16	1.29	2.20		.07	1	34	36	.01		.04			
520.2	522.3	75794	2.1	.0 2C3	3.92	.36	.66	1.01	10.90		.07	1	30	32	.02		.05			

DDH: 81-19 UTM-N: 8102.2 UTM-E: 15699.7 UTM-ELEV: 4101.3 TOTAL DEPTH: 624.0 SECTION: 130
RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	ASSAYS													
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %
522.3	524.5	75795	2.2	.0	2C3	4.13	.48	.35	.84	8.70		.07	1	34	35	.04		.01		
524.5	526.6	75796	2.1	.0	2C3	4.05	.24	.23	.10	9.30		.07		33	34	.04		.01		
526.6	528.7	75797	2.1	.0	2C3	4.06	.18	1.22	.93	9.00		.07	2	31	34	.02		.06		
528.7	530.8	75798	2.1	.0	2C3	4.25	.16	.47	1.18	4.00		.07	2	34	37	.02		.06		
530.8	533.1	75799	2.3	.0	2F4	3.74	.09	3.19	8.13	10.30		.07	2	22	24	.07		.03		
533.1	535.4	75800	2.3	.0	2F4	3.82	.08	5.00	10.20	12.10		.17	2	21	23	.04		.03		
535.4	537.5	75801	2.1	.0	2D0	3.58	.05	2.04	5.55	15.90		.07	1	20	22	.11		.03		
537.5	540.7	75802	3.2	.0	2D4	3.51	.12	4.98	12.80	33.90		.07	4	11	16	.10		.05		
540.7	543.8	75803	3.1	.0	2D0	3.12	.09	1.78	2.55	15.90		.07	5	9	14	.16		.04		
543.8	546.9	75804	3.1	.0	2L4	2.93	.10	1.23	4.01	19.00		.34	4	4	8	.24		.05		
546.9	550.0	75805	3.1	.0	2L4	2.97	.11	1.72	4.42	24.30		.55	3	3	7	.34		.05		
550.0	553.1	75806	3.1	.0	2L3	2.82	.07	1.44	1.50	22.70		.27	1	2	3	2.03		.01		
553.1	556.2	75807	3.1	.0	2L3	2.76	.05	1.22	1.81	19.00		.27	1	1	2	.46		.01		
556.2	559.2	75808	3.0	.0	2L3	2.78	.04	1.51	2.53	16.50		.41	1	1	2	.47		.01		
559.2	562.2	75809	3.0	.0	2L3	2.74	.04	1.05	2.20	23.60		.69		1	2	.47		.01		
562.2	565.9	75810	3.7	.0	2A0	2.73	.07	1.29	2.49	19.90		.55	1	1	3	.40		.01		
565.9	568.9	75811	3.0	.0	2L4	2.90	.14	1.08	3.47	20.20		.27	2	4	7	.31		.03		
568.9	571.9	75812	3.0	.0	2L1	2.76	.05	1.05	2.74	14.90		.07	1	1	2	.50		.02		
571.9	574.8	75813	2.9	.0	2L1	2.80	.04	.46	.66	8.70		.07	2	2	5	.38		.09		
574.8	577.7	75814	2.9	.0	2L1	2.78	.11	.55	1.38	11.20		.07	2	2	4	.40		.02		

DDH: 81-20 UTM-N: 7733.0 UTM-E: 15533.0 UTM-ELEV: 4017.9 TOTAL DEPTH: 421.0 SECTION: 131
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

---DEPTHS---		SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														S.G. W.R.
FROM	TO					Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	
221.8	224.5	75820	2.7	.0 2H34	3.79	.38	4.53	5.19	73.10		.07	12	16	28	2.27		.16			
224.5	227.3	75821	2.8	.0 2H34	4.36	.29	5.12	8.90	59.70		.07	31	9	41	.07		.13			
227.3	229.8	75822	2.5	.0 2E74	4.28	.24	5.32	8.47	61.30		.07	16	19	36	.02		.13			
229.8	232.4	75823	2.6	.0 2E74	4.30	.35	4.76	8.19	61.60		.07	14	21	36	.02		.15			
232.4	236.7	75824	4.3	.0 2H34	4.29	.28	5.04	8.93	65.90		.07	30	9	40			.12			
236.7	239.9	75825	3.2	.0 2F4	4.38	.05	5.10	7.75	53.50		.07	2	30	33	.01		.05			
239.9	246.3	75826	6.4	.0 2F4	4.66	.03	6.96	13.70	58.80		.07	2	29	31	.02		.02			
246.3	249.5	75827	3.2	.0 2F4	4.69	.03	8.24	12.60	67.50		.07	1	30	32	.01		.02			
249.5	252.7	75828	3.2	.0 2F4	4.74	.06	3.59	8.06	28.60		.07	1	36	37	.01		.02			
252.7	255.9	75829	3.2	.0 2F4	4.54	.11	3.31	6.78	31.70		.07	3	32	36	.01		.10			
255.9	257.3	75830	1.4	.0 2F4	4.26	.34	4.82	8.94	50.40		.07	29	9	38	.01		.27			
257.3	260.5	75831	3.2	.0 2F4	4.67	.23	6.23	12.20	50.40		.07	3	29	33	.01		.08			
260.5	263.6	75832	3.1	.0 2F4	4.64	.10	4.10	7.87	41.10		.07	3	33	36	.01		.07			
263.6	264.6	75833	1.0	.0 2H4	4.30	.40	3.92	7.06	39.20		.07	30	11	41	.21		.10			
264.6	267.6	75834	3.0	.0 2FE	4.60	.11	1.98	5.66	21.80		.07	3	34	38	.01		.08			
267.6	270.2	75835	2.6	.0 2D5	3.20	.40	.54	4.82	11.80		.07	5	11	16	.23		.07			
270.2	272.8	75836	2.6	.0 2D5	3.07	.18	2.18	6.88	27.70		.07	4	6	10	.31		.05			
272.8	275.4	75837	2.6	.0 2D5/4	2.98	.08	2.79	8.26	34.20		.34	3	4	7	.22		.03			
275.4	277.9	75838	2.5	.0 2D5	2.99	.07	2.24	4.78	30.50		.27	3	5	9	.21		.03			
277.9	281.4	75839	3.5	.0 2A14	3.00	.10	1.73	4.72	28.00		.27	4	6	10	.16		.02			
281.4	284.9	75840	3.5	.0 2A14	2.92	.07	.97	3.74	18.00		.07	3	5	8	.16		.02			
284.9	288.4	75841	3.5	.0 2A14	2.92	.05	3.39	6.63	39.80		.14	2	3	6	.15		.02			
288.4	291.9	75842	3.5	.0 2A14	2.97	.07	1.47	4.78	29.60		.27	3	6	10	.15		.03			
291.9	295.2	75843	3.3	.0 2A4	2.86	.06	1.75	4.50	28.00		.07	4	3	7	.21		.06			
295.2	298.5	75844	3.3	.0 2A4	2.77	.05	1.69	4.67	29.60		.27	2	2	4	.17		.03			
298.5	301.8	75845	3.3	.0 2A4	2.77	.03	1.70	3.33	21.50		.34	1	2	4	.15		.03			
301.8	305.2	75846	3.4	.0 2A4	2.83	.07	1.19	2.53	25.80		.27	2	5	7	.14		.03			
305.2	308.6	75847	3.4	.0 2A4	2.87	.05	1.27	3.46	21.50		.27	4	2	7	.29		.05			
308.6	312.0	75848	3.4	.0 2A4	2.74	.04	1.54	3.83	23.00		.41	2	2	4	.18		.03			
312.0	314.4	75849	2.4	.0 2A0	2.76	.05	1.28	1.38	25.80		.07	3	2	5	.28		.04			
314.4	316.7	75850	2.3	.0 2A0	2.74	.05	1.16	1.24	21.20		.17	3	2	5	2.02		.05			
316.7	319.0	75851	2.3	.0 2A4	2.74	.04	2.20	2.06	31.10		.48	2	2	5	.24		.03			
319.0	324.9	75852	5.9	.0 2A0	2.59	.02	.70	1.02	9.60		.07	1		2	2.36		.02			
324.9	327.2	75853	2.3	.0 2A0	2.65	.02	.92	2.47	12.40		.07	1		2	.29		.07			
327.2	328.5	75854	1.3	.0 2A0	2.69	.03	1.14	2.83	21.20		.07	2	1	3	2.02		.02			
335.0	336.0	75856	1.0	.0 2A0	2.86	.12	.32	.58	12.10		.07	3	6	9	.10		.02			

DDH: 81017 UTM-N: 7734.0 UTM-E: 15529.4 UTM-ELEV: 4017.7 TOTAL DEPTH: 248.0 SECTION:
RFE: RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS----						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
210.0	212.9	75677	2.9	.0	****	2.72	.02	.40	.51	.80		.07	1	2	4	3.27		.05			
226.4	227.6	75679	1.2	.0	****	3.08	.10	1.14	2.53	18.70		.07	5	10	15	2.69		.06			
227.6	229.6	75680	2.0	.0	****	4.32	.22	4.61	7.98	52.90		.07	14	25	40	.07		.10			
229.6	232.6	75681	3.0	.0	****	3.14	.03	.72	3.07	12.10		.07	1	15	16	.04		.02			
232.6	238.8	75682	6.2	.0	****	4.63	.03	5.84	9.85	46.30		.07	1	36	38	.01		.04			
238.8	245.0	75683	6.2	.0	****	4.73	.11	5.31	9.26	37.90		.07	1	38	40	.01		.03			
245.0	248.0	75684	3.0	.0	****	4.73	.03	5.97	9.69	42.30		.07	1	33	35	.01		.02			

DDH: 82F-01 UTM-N: 8841.5 UTM-E: 15313.2 UTM-ELEV: 4071.3 TOTAL DEPTH: 903.0 SECTION: 124
RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

-----DEPTHS-----						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
532.5	537.6	82001	5.1	5.1	2C07	3.57	.26	.54	2.07	11.82		.10	5	19	25	.13		.08			
537.6	542.7	82002	5.1	5.1	2C07	3.33	.18	.12	1.81	8.09		.04	8	12	21	.02		.03			
542.7	547.8	82003	5.1	5.1	2C07	3.57	.19	.23	1.81	8.09		.10	8	16	25	.01		.06			
547.8	552.9	82004	5.1	5.1	2C07	3.57	.14	.32	1.29	7.78		.07	6	17	23	.06		.03			
552.9	556.7	82005	3.8	3.8	2D4	3.45	.05	4.08	12.40	19.91		.10	3	11	15	.10		.02			
556.7	560.7	82006	4.0	4.0	2CE4	4.22	.06	2.48	6.14	19.28		.04	4	24	28	.06		.04			
560.7	564.6	82007	3.9	3.7	2CE4	4.00	.08	3.65	10.34	30.79		.07	4	21	26	.06		.04			
564.6	567.7	82008	3.1	3.1	2L34	3.05	.13	2.15	3.72	30.79		.10	4	5	9	.20		.03			
567.7	570.8	82009	3.1	3.0	2L3	2.81	.07	.24	.22	9.02		.04	2	3	5	.14		.02			
570.8	575.0	82010	4.2	4.2	2B45	2.94	.11	1.18	4.29	21.77		.07	4	3	7	.19		.02			
575.0	579.2	82011	4.2	4.2	2B45	2.95	.10	1.93	4.93	51.01		1.30	3	2	5	.21		.01			
579.2	583.2	82012	4.0	4.0	2A0	2.88	.16	.67	2.35	16.17		.14	4	4	8	.17		.01			
583.2	587.2	82013	4.0	4.0	2A0	2.78	.14	.52	1.06	10.58		.04	3	3	7	.11		.01			
587.2	591.2	82014	4.0	3.9	2A0	1.79	.08	.65	.91	11.82		.04	2	2	5	.11		.01			
591.2	595.3	82015	4.1	3.7	2A4	2.92	.13	1.86	2.90	64.07		1.27	3	2	6	.15		.05			
600.8	604.8	82016	4.0	4.0	2B05	2.83	.05	.91	1.67	18.97		.07	2	1	4	.24		.03			
604.8	608.9	82017	4.1	4.1	2L14	2.79	.11	.70	1.19	19.91		.04	2	2	5	.13		.01			

DDH: 82F-03 UTM-N: 8289.8 UTM-E: 15294.0 UTM-ELEV: 4031.0 TOTAL DEPTH: 627.0 SECTION: 127
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
394.8	398.3	82018	3.5	3.5	2GE4	4.43	.10	5.37	9.25	101.40		.10	3	19	22	9.96		.12			
423.4	428.3	82019	4.9	4.9	2H46	3.82	.20	2.32	2.40	51.32		.07	10	15	26	4.83		.14			
428.3	432.0	82020	3.7	3.7	2E48	4.72	.24	2.31	2.60	34.52		.10	8	28	36	.15		.29			
432.0	436.3	82021	4.3	4.1	2E8	4.67	.36	1.49	1.38	29.86		.04	5	30	36	.03		.17			
436.3	441.0	82022	4.7	4.7	2E0	4.53	.09	.88	.60	16.79			1	32	34	.08		.02			
441.0	449.7	82023	8.7	8.4	2E0	4.51	.08	.77	.42	12.75			1	33	34	.07		.02			
449.7	456.9	82024	7.2	7.2	2C3	3.73	.13	.35	.33	16.49				23	24	.03		.01			
456.9	464.5	82025	7.6	7.6	2C3	3.86	.05	.84	.50	18.35				25	26	.02		.01			
464.5	465.3	82026	.8	.8	2H19	3.75	.59	1.06	.23	15.55			30	8	38			.03			
465.3	470.5	82027	5.2	5.2	2CE0	3.92	.09	1.36	1.84	21.46		.14	2	24	26	.01		.02			
470.5	475.7	82028	5.2	5.2	2CE0	3.94	.05	1.15	1.00	29.55		.69		26	26	.01		.01			
475.7	480.8	82029	5.1	5.1	2CE0	3.32	.17	2.69	1.01	140.59		5.08		14	15	.01		.01			
480.8	485.9	82030	5.1	5.1	2CE0	3.92	.12	1.66	1.99	22.08		.07	1	24	26	.03		.04			
485.9	491.0	82031	5.1	5.1	2CE4	4.13	.08	2.55	4.65	22.08		.04	2	25	27	.05		.04			
491.0	497.2	82032	6.2	6.2	2A14	3.41	.03	2.35	4.68	30.17		.10	1	13	14	.24		.01			
497.2	501.8	82033	4.6	4.6	2CE4	4.26	.20	1.64	2.92	18.35		.04	5	25	31	.01		.17			
501.8	506.4	82034	4.6	4.6	2CE4	4.00	.37	1.74	2.83	18.97		.04	5	22	27	.01		.20			
506.4	511.0	82035	4.6	4.6	2CE8	3.91	.56	1.12	1.60	20.84		.04	5	21	26	.01		.14			
511.0	515.2	82036	4.2	4.2	2F10	4.55	.17	3.58	5.93	28.30		.04	7	24	31	.02		.29			
515.2	519.3	82037	4.1	4.1	2F14	4.19	.21	5.30	7.08	34.53		.04	5	20	26			.15			
519.3	523.4	82038	4.1	4.1	2F14	4.53	.20	6.30	10.03	40.44		.04	7	20	28	.01		.31			
523.4	528.6	82039	5.2	5.2	2CE0	4.33	.21	1.38	2.54	9.64		.04	6	25	32	.01		.18			
528.6	533.7	82040	5.1	5.1	2CE0	3.89	.33	.40	1.10	8.71		.14	4	23	27	.02		.11			
533.7	538.8	82041	5.1	5.1	2CE0	3.94	.39	.39	1.69	7.15		.04	4	23	27	.07		.10			
538.8	543.1	82042	4.3	4.3	2D34	4.15	.15	3.40	8.47	12.75		.04	3	21	25	.01		.05			
543.1	547.3	82043	4.2	4.2	2D34	4.48	.09	4.67	8.83	15.24		.04	2	25	27	.03		.02			
547.3	551.5	82044	4.2	4.2	2D34	4.24	.07	6.02	10.64	19.28		.04	3	21	24	.02		.02			
551.5	554.8	82045	3.3	3.3	2D34	4.15	.08	1.51	4.34	7.15		.04	2	24	27	.01		.03			
554.8	558.2	82046	3.4	3.4	2D34	4.07	.06	5.22	10.09	24.88		.04	2	18	21	.05		.03			
558.2	562.7	82047	4.5	4.5	2B05	2.87	.11	.82	1.44	22.08		.34	2	1	4	.31		.03			
562.7	567.2	82048	4.5	4.5	2B05	2.92	.12	1.79	1.57	26.44		.14	2	2	4	.24		.02			
567.2	571.7	82049	4.5	4.5	2B05	2.94	.15	.41	1.49	12.13		.14	3	3	7	.18		.01			
571.7	576.2	82050	4.5	4.5	2B05	2.92	.22	.44	1.37	19.60		.28	3	3	6	.17		.02			
576.2	580.5	82051	4.3	4.3	2D4	3.41	.29	3.23	10.10	39.19		.21	4	8	13	.09		.03			

DDH: 82F-05 UTM-N: 7889.3 UTM-E: 14894.5 UTM-ELEV: 3913.1 TOTAL DEPTH: 407.0 SECTION: 127
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

---DEPTHS---							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
273.2	277.7	82052	4.5	4.5	2A4	3.25	.30	.62	3.83	14.61		.10	5	10	15	.04		.03			
277.7	282.2	82053	4.5	4.5	2A4	2.89	.06	5.18	9.88	30.17		.28	2	9	11	.05		.01			
282.2	287.2	82054	5.0	4.8	2E24	4.82	.08	3.14	3.52	36.08		.07	2	26	28	.02		.04			
287.2	291.4	82055	4.2	4.2	2E74	4.45	.20	6.32	8.47	130.33		.14	9	16	25	1.12		.24			
291.4	296.8	82056	5.4	5.4	2B4	3.12	.15	3.37	7.55	49.46		.07	4	4	8	.22		.15			
296.8	302.2	82057	5.4	4.7	2B4	2.86	.06	2.47	3.87	30.01		.07	2	2	5	.07		.05			
302.2	306.6	82058	4.4	4.4	2E4	4.45	.32	6.42	7.38	113.53		.17	12	14	26	.09		.32			
306.6	310.2	82059	3.6	3.6	2H4	4.40	.42	4.39	6.93	69.36		.07	38		39	.54		.14			
310.2	313.7	82060	3.5	3.0	2H4	4.39	.41	2.92	3.39	51.32		.10	40	2	42	.05		.06			
313.7	318.7	82061	5.0	4.9	2H4	4.40	.52	2.62	3.87	48.83		.10	43		43	.03		.05			
318.7	323.7	82062	5.0	5.0	2H4	4.44	.50	2.87	4.31	53.81		.10	43		44	.03		.06			
323.7	328.7	82063	5.0	5.0	2H4	4.23	.55	2.64	2.76	60.03		.14	40		40	.02		.06			
328.7	333.9	82064	5.2	5.2	2H4	4.41	.42	3.38	5.35	61.51		.14	42		42	.01		.08			
333.9	338.8	82065	4.9	4.9	2B57	3.03	.26	.52	1.76	21.77		.10	10	1	12	.25		.01			
338.8	344.0	82066	5.2	5.2	2B5	2.87	.13	.72	1.55	14.00		.07	5	2	8	.29		.01			
344.0	349.0	82067	5.0	5.0	2A0	2.69	.04	.36	.93	12.44		.07	4		4	.43		.05			
349.0	354.0	82068	5.0	5.0	2A0	2.69	.02	.59	1.50	6.53		.04	1	1	3	.54		.02			
354.0	359.0	82069	5.0	5.0	2A4	2.77	.08	1.38	2.94	25.82		.10	2	1	3	.71		.02			
359.0	363.9	82070	4.9	4.9	2A0	2.77	.03	.82	1.71	16.49		.17	2	2	4	.44		.01			

DDH: 82F-06 UTM-N: 8467.3 UTM-E: 14924.0 UTM-ELEV: 4069.0 TOTAL DEPTH: 792.0 SECTION: 124
 RFE: S2 RFE DIR: 200 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	ASSAYS														
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
462.2	464.6	82071	2.4	2.2	2DE	3.38	.21	1.38	4.34	16.17		.14	14	7	22	.55		.09			
464.6	469.0	82072	4.4	4.4	2G0	4.63	.03	3.15	5.37	32.04		.14	1	16	17	29.87		.01			
469.0	473.5	82073	4.5	4.5	2G4	4.59	.06	4.17	6.33	56.92		.10		10	11	42.93		.01			
473.5	476.8	82074	3.3	3.3	2E4	4.51	.03	4.13	6.36	42.30		.10	1	28	29	2.26		.01			
476.8	480.0	82075	3.2	3.0	2E4	4.60	.03	4.57	7.68	52.25		.07	1	25	27	2.99		.01			
480.0	484.8	82076	4.8	4.8	2G0	3.48	.04	2.85	5.07	30.48		.10		14	15	37.90		.01			
484.8	489.6	82077	4.8	4.8	2G4	4.51	.05	3.56	6.52	57.23		.10	2	16	18	26.42		.06			
512.0	515.9	82078	3.9	3.9	2A0	2.73	.02	.39	.38	4.04			2	2	4	2.87		.02			
515.9	519.8	82079	3.9	3.9	2A0	2.74	.02	.23	.30	5.91			2	2	4	2.80		.02			
519.8	525.9	82080	6.1	6.1	2L0	3.04	.05	.81	1.00	12.75			4	4	8	2.87		.08			
525.9	528.9	82081	3.0	3.0	2A0	2.78	.03	.45	.36	6.22			1	2	3	3.38		.03			
528.9	533.0	82082	4.1	4.1	2L41	2.92	.06	1.19	1.94	17.42		.10	4	3	7	4.72		.10			
533.0	537.1	82083	4.1	4.1	2E4	4.44	.13	4.75	6.40	75.58		.14	8	19	27	6.19		.11			
537.1	541.2	82084	4.1	4.1	2E4	4.08	.23	4.63	6.52	71.54		.14	12	17	29	.16		.09			
541.2	545.3	82085	4.1	4.1	2E4	4.33	.30	5.72	8.17	100.46		.14	21	11	33	.57		.07			
545.3	548.8	82086	3.5	3.5	2D0	2.84	.06	1.62	2.50	41.99		.10	3	2	6	.12		.03			
548.8	552.2	82087	3.4	3.4	2D07	2.87	.14	3.90	2.96	122.55		.17	8	7	15	.47		.07			
552.2	555.7	82088	3.5	3.5	2E47	4.38	.15	4.33	5.02	95.49		.21	7	22	30	.38		.14			
555.7	559.1	82089	3.4	3.4	2E07	4.15	.28	.63	.44	12.75			16	18	34	.01		.09			
559.1	563.4	82090	4.3	4.3	2H0	4.36	.43	.75	.21	18.97			37	6	43	.01		.11			
563.4	567.2	82091	3.8	3.8	2E0	4.71	.15	1.05	.74	21.46			7	28	35	.01		.19			
567.2	569.5	82092	2.3	2.3	2E8	4.70	.11	1.09	1.07	25.19		.14	9	27	36	.03		.33			
569.5	575.0	82093	5.5	5.5	2E4	4.48	.28	3.32	4.72	59.41		.10	9	24	33	.01		.27			
575.0	580.5	82094	5.5	4.0	2E48	4.58	.20	2.06	2.74	37.95		.07	9	25	34	.01		.37			
580.5	589.9	82095	9.4	5.7	2F0	4.48	.16	2.73	3.89	39.50		.07	1	30	32	.01		.01			
589.9	604.0	82096	14.1	6.0	2F0	4.76	.06	3.22	6.03	36.08		.04	1	32	33	.02		.02			
604.0	608.4	82097	4.4	3.4	2F4	4.70	.07	4.76	9.66	44.48		.07	2	29	31	.02		.02			
608.4	612.8	82098	4.4	3.2	2F4	4.89	.03	4.07	7.88	41.06		.04	1	31	33	.35		.02			
612.8	615.5	82099	2.7	2.2	2G0	4.85	.03	2.71	6.83	29.24		.04	1	25	27	11.08		.03			
615.5	617.8	82100	2.3	2.0	2E41	4.23	.16	2.90	3.42	31.73		.04	3	26	30	.30		.13			
617.8	622.0	82101	4.2	4.1	2F4	4.76	.10	5.43	10.60	65.32		.07	4	25	29	.03		.09			
622.0	625.4	82102	3.4	3.4	2H43	4.31	.54	4.13	8.87	48.21		.04	29	8	37	.03		.17			
625.4	629.4	82103	4.0	4.0	2F41	4.63	.17	4.26	9.11	36.08		.04	6	24	30	.04		.16			
629.4	633.4	82104	4.0	4.0	2G41	4.53	.19	3.28	7.52	37.64		.07	4	21	26	9.37		.15			
633.4	637.4	82105	4.0	4.0	2G0	4.49	.15	2.61	5.60	31.73		.07	3	23	26	7.03		.09			
637.4	641.8	82106	4.4	4.4	2F4	4.46	.17	4.24	9.28	32.04		.07	4	24	28	1.20		.14			
641.8	646.3	82107	4.5	4.5	2F4	4.89	.14	4.70	8.90	39.81		.04	2	26	29	3.45		.08			
646.3	650.8	82108	4.5	4.5	2F0	4.66	.19	3.27	6.28	34.46		.04	6	26	33	.89		.25			
650.8	655.3	82109	4.5	4.5	2F4	4.79	.22	5.69	8.30	51.32		.04	5	24	29	3.94		.21			
655.3	660.3	82110	5.0	5.0	2F0	4.57	.17	2.77	6.19	21.46		.07	4	27	31	.06		.09			
660.3	665.3	82111	5.0	5.0	2F0	3.99	.26	2.95	5.94	34.21		.07	13	18	31	.04		.09			
665.3	670.3	82112	5.0	5.0	2F4	4.66	.06	3.19	6.71	22.08		.07	3	31	34	.01		.03			
670.3	675.3	82113	5.0	5.0	2F4	4.71	.12	4.42	8.35	32.35		.07	5	26	31	.03		.02			
675.3	679.2	82114	3.9	3.9	2D3	3.04	.07	2.13	4.15	27.05		.14	4	6	11	.53		.06			
679.2	683.1	82115	3.9	3.9	2D3	3.12	.05	1.71	4.74	21.46		.10	4	8	12	.16		.03			
683.1	687.0	82116	3.9	3.9	2D34	3.37	.03	2.11	8.26	33.90		.28	3	13	16	.16		.02			
687.0	690.8	82117	3.8	3.8	2D5	3.04	.05	1.57	5.37	24.88		.17	3	3	6	.28		.01			
690.8	694.7	82118	3.9	3.9	2D5	2.97	.06	2.19	5.73	30.48		.07	4	5	9	.18		.01			
694.7	697.0	82119	2.3	2.3	2A4	3.09	.03	2.75	6.70	35.15		.28	3	3	6	.30		.02			
697.0	702.3	82120	5.3	5.3	2D3	3.31	.06	2.69	6.03	35.77		.17	4	11	16	.16		.01			

DDH: 82F-06 UTM-N: 8467.3 UTM-E: 14924.0 UTM-ELEV: 4069.0 TOTAL DEPTH: 792.0 SECTION: 124
RFE: S2 RFE DIR: 200 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS----						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
702.3	707.6	82121	5.3	5.3	2D3	3.21	.20	2.75	4.99	50.70		.28	6	7	13	.21		.03			
707.6	712.9	82122	5.3	5.3	2D3	3.22	.09	2.95	5.57	37.64		.10	4	8	12	.17		.01			
712.9	718.3	82123	5.4	5.4	2D43	3.40	.05	3.63	6.84	40.12		.17	4	11	15	.12		.03			
718.3	723.7	82124	5.4	5.4	2D3	3.42	.04	2.01	6.85	27.99		.14	4	11	16	.12		.02			
723.7	729.1	82125	5.4	5.4	2D3	3.26	.06	2.55	5.81	35.46		.21	5	9	14	.16		.01			
729.1	734.5	82126	5.4	5.4	2D43	3.39	.08	3.90	6.90	46.35		.17	6	7	14	.09		.01			
734.5	739.2	82127	4.7	4.7	2C35	3.33	.13	1.31	3.19	17.11		.10	10	8	18	.07		.02			
739.2	743.9	82128	4.7	4.7	2C35	3.50	.08	2.51	4.32	36.08		.14	4	14	19	.06		.01			
743.9	748.6	82129	4.7	4.7	2C35	3.21	.11	1.56	2.90	29.55		.10	8	6	15	.11		.01			
748.6	753.3	82130	4.7	4.7	2C35	3.13	.11	1.19	3.75	28.93		.07	5	7	13	.07		.01			
753.3	756.4	82131	3.1	3.1	2A41	2.89	.06	1.91	4.99	33.28		.62	2	2	5	.11		.01			
756.4	759.4	82132	3.0	3.0	2A41	2.86	.06	1.70	2.86	33.90		.21	4	2	6	.17		.04			

DDH: 82F-07 UTM-N: 7890.6 UTM-E: 14693.4 UTM-ELEV: 3912.8 TOTAL DEPTH: 422.0 SECTION: 126
RFE: S2 RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----						-----ASSAYS-----																	
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.		
337.1	340.5	82133	3.4	3.4	2A0	3.26	.27	.06	.08	13.47				3 13	17	.11		.05					
340.5	343.9	82134	3.4	3.4	2C5	3.55	.34	.34	.91	22.40				2 21	23	.03		.03					
343.9	348.9	82135	5.0	4.5	2A41	3.24	.19	1.53	5.71	33.28		.21	4	10	15	.03		.06					
348.9	352.1	82136	3.2	2.6	2F0	3.19	.12	1.84	5.99	25.19		.41	3	9	12	.08		.05					
352.1	355.3	82137	3.2	3.2	2A0	3.06	.12	1.02	2.34	37.01		.72	1	9	10	.17		.02					
355.3	359.6	82138	4.3	4.3	2F4	4.81	.17	6.21	6.72	84.91		.14	5	27	32	.54		.28					
359.6	363.9	82139	4.3	4.3	2F4	4.55	.13	4.83	5.98	83.36		.14	7	17	25	6.17		.27					
363.9	368.4	82140	4.5	4.5	2B4	2.96	.16	2.88	3.50	42.61		.10	3	3	7	1.15		.01					
368.4	372.6	82141	4.2	4.0	2A4	3.04	.07	1.59	4.97	29.55		.07	4	5	10	.20		.01					
372.6	376.9	82142	4.3	4.3	2A0	2.89	.03	1.10	2.15	22.08		.07	4	3	7	.47		.01					
376.9	381.2	82143	4.3	4.3	2A0	2.82	.04	.96	2.62	18.66		.10	3	2	6	.40		.03					
381.2	385.5	82144	4.3	4.3	2A4	2.95	.08	1.88	2.93	34.84		.10	5	4	9	.23		.04					

DDH: 82F-08 UTM-N: 8091.1 UTM-E: 14697.7 UTM-ELEV: 3908.9 TOTAL DEPTH: 541.0 SECTION: 125
 RFE: S2 RFE DIR: 200 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	ASSAYS														
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
361.9	366.1	82145	4.2	4.2	2CE0	3.32	.24	.08	.07	17.11			1	17	18	.01		.02			
366.1	369.6	82146	3.5	3.5	2C3	3.77	.18	.03	.03	10.89			5	21	26	.02		.05			
369.6	373.0	82147	3.4	3.4	2C3	3.62	.41	.42	.26	15.86			11	14	26	.02		.08			
373.0	378.1	82148	5.1	5.1	2E4	4.12	.23	4.57	6.58	76.20			7	18	26	2.55		.31			
378.1	383.4	82149	5.3	5.3	2C56	2.77	.02	.68	.57	6.53			2	2	4	4.04		.06			
383.4	388.9	82150	5.5	5.5	2L14	3.00	.02	2.00	2.57	36.08			4	3	7	3.16		.08			
388.9	393.9	82151	5.0	4.9	2A0	2.81	.01	.60	.69	8.40			3	2	5	3.13		.03			
393.9	398.9	82152	5.0	4.5	2A0	2.89	.01	.55	.73	8.40			2	1	4	3.01		.04			
398.9	402.4	82153	3.5	3.5	2L0	3.08	.06	.95	.64	16.49			4	5	9	2.55		.04			
402.4	406.0	82154	3.6	3.4	2L0	3.01	.03	.48	.67	7.15			2	2	5	3.36		.03			
406.0	410.1	82155	4.1	4.0	2L14	3.14	.07	1.83	2.18	31.42		.07	4	4	9	7.92		.09			
410.1	414.2	82156	4.1	4.1	2L14	3.16	.06	2.88	2.42	62.52		.07	6	4	11	4.51		.13			
414.2	419.7	82157	5.5	5.5	2H4	3.73	.15	6.67	6.10	135.92		.07	21	2	24	.12		.16			
419.7	425.2	82158	5.5	5.5	2H4	3.94	.25	4.39	7.73	90.20		.07	22	7	29	.19		.14			
425.2	430.7	82159	5.5	5.4	2H4	4.48	.31	6.86	7.15	148.05		.07	24	8	32	3.61		.24			
430.7	436.3	82160	5.6	5.6	2E42	4.80	.11	2.97	3.82	33.59		.07	7	29	36	.05		.08			
436.3	441.9	82161	5.6	5.4	2E42	4.70	.20	2.75	4.16	39.50		.07	12	26	39	.07		.07			
441.9	445.6	82162	3.7	3.7	2D5	3.07	.20	3.05	6.08	72.16		.10	5	6	11	.18		.06			
445.6	449.7	82163	4.1	4.1	2D5	3.16	.20	1.07	3.22	29.86		.07	8	3	11	.23		.05			
449.7	451.9	82164	2.2	2.2	2H4	4.36	.51	2.78	4.41	40.44		.07	42	2	44	.02		.12			
451.9	457.6	82165	5.7	5.7	2E2	4.63	.65	1.12	1.82	20.53		.10	12	25	38	.03		.17			
457.6	463.2	82166	5.6	5.6	2E2	4.18	.27	.83	3.60	10.26		.07	5	27	33	.03		.14			
463.2	468.8	82167	5.6	5.6	2E2	4.80	.14	3.00	4.82	18.04		.07	2	31	34	.02		.06			
468.8	472.4	82168	3.6	3.6	2D4	3.33	.13	.52	3.50	9.64		.14	3	14	17	.16		.03			
472.4	474.2	82169	1.8	1.8	2E0	4.44	.21	.18	2.21	7.78		.07	3	31	35	.04		.04			
474.2	476.4	82170	2.2	2.2	2L0	3.04	.19	.96	.48	14.00		.07	5	9	14	.15		.01			
476.4	480.0	82171	3.6	3.6	2E4	4.34	.22	4.97	8.00	99.22		.14	9	22	31	.02		.09			
496.0	498.5	82172	2.5	2.4	2A1	2.93	.11	.13	.31	10.58			4	3	8	.11		.03			
498.5	502.0	82173	3.5	3.5	2L0	2.86	.04	.03	.06	6.53			2	1	3	.19		.01			
502.0	505.6	82174	3.6	3.6	2C5	2.88	.15	.34	.37	51.01			5	5	10	.15		.03			
505.6	509.3	82175	3.7	3.7	2C5	3.08	.18	.14	.11	13.38			7	7	14	.10		.05			
509.3	514.4	82176	5.1	5.1	2A0	2.93	.13	.33	.16	9.64			5	2	8	.18		.01			
514.4	519.5	82177	5.1	5.1	2A0	2.97	.13	1.39	.48	27.99			5	3	9	.16		.01			
519.5	524.8	82178	5.3	5.1	2A41	2.75	.03	1.54	3.10	13.69			1		1	.19		.01			
524.8	530.0	82179	5.2	4.0	2A1	2.87	.07	1.16	2.40	26.13			2	1	4	.20		.03			

DDH: 82F-09 UTM-N: 8296.2 UTM-E: 14692.8 UTM-ELEV: 4040.1 TOTAL DEPTH: 667.0 SECTION: 124
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %
491.2	495.8	82180	4.6	4.6	2E4	3.70	.18	2.74	4.79	42.61		.10	6	12	19	2.79		.12		
495.8	500.3	82181	4.5	4.5	2E4	4.41	.12	4.83	4.26	79.00		.17	7	16	23	4.38		.39		
500.3	504.8	82182	4.5	4.5	2E4	4.29	.21	6.63	5.58	107.93		.10	8	12	20	8.48		.45		
504.8	509.5	82183	4.7	4.7	2A0	2.83	.01	.25	.30	5.91			2	1	4	2.45		.07		
509.5	514.3	82184	4.8	4.8	2A0	2.79	.02	.40	.52	6.53			2	2	4	2.52		.06		
514.3	519.1	82185	4.8	4.8	2A0	2.79	.03	.51	.80	7.78			2	2	4	1.35		.06		
519.1	523.9	82186	4.8	4.8	2A0	2.68	.02	.25	.30	.93			2	1	3	2.34		.02		
530.4	533.4	82187	3.0	3.0	2D4	3.47	.13	6.35	7.05	137.79		.07	8	5	14	.73		.21		
536.5	540.6	82188	4.1	4.1	2B0	2.87	.04	.86	1.61	10.26		.04	3	2	5	.26		.05		
540.6	544.7	82189	4.1	4.1	2B0	3.03	.06	1.20	2.35	21.46		.04	3	4	8	.08		.06		
547.7	552.2	82190	4.5	4.0	2B4	3.19	.14	8.38	1.95	144.01		.14	5	5	10	.05		.10		
552.2	556.6	82191	4.4	4.2	2B4	3.27	.10	7.90	3.39	162.67		.10	4	6	11	.07		.10		
556.6	561.5	82192	4.9	4.9	2B4	3.09	.08	3.67	1.96	69.05		.04	4	3	8	.07		.06		
561.5	566.4	82193	4.9	4.9	2B0	3.08	.09	.76	1.72	17.11		.04	7	4	11	.46		.09		
566.4	571.2	82194	4.8	4.8	2C0	3.21	.24	.84	1.95	13.37		.07	8	8	16	.18		.07		
571.2	574.2	82195	3.0	3.0	2E42	4.72	.15	3.30	5.63	35.46		.04	4	28	32	.02		.09		
574.2	577.3	82196	3.1	3.1	2E42	4.81	.13	3.57	6.51	36.39		.04	3	29	33	.02		.06		
577.3	581.7	82197	4.4	4.4	2H4	4.51	.45	2.29	4.15	29.24		.04	24	14	38	.03		.14		
581.7	586.1	82198	4.4	4.4	2H4	4.51	.48	3.79	6.46	31.10		.04	29	8	37	.03		.09		
586.1	590.5	82199	4.4	4.4	2H4	4.51	.62	2.66	5.06	35.15		.04	24	14	38	.02		.16		
590.5	596.0	82200	5.5	5.5	2E2	4.18	.27	1.94	3.58	14.31		.04	7	23	31	.05		.17		
596.0	600.5	82201	4.5	4.5	2A0	3.20	.16	1.06	2.06	22.71		.04	10	4	15	.14		.15		
600.5	604.9	82202	4.4	4.4	2A0	3.14	.11	.94	2.10	22.71		.04	6	7	13	.18		.08		
604.9	609.3	82203	4.4	4.4	2A4	3.08	.10	1.48	2.53	40.12		.04	5	6	12	.16		.05		
609.3	612.6	82204	3.3	3.3	2C0	3.00	.08	.62	2.62	19.91		.04	5	4	10	.21		.05		
612.6	615.9	82205	3.3	3.3	2D0	3.13	.14	3.17	4.87	93.62		.04	5	6	12	.20		.03		
615.9	619.2	82206	3.3	3.3	2A0	2.83	.05	1.11	2.82	25.82		.04	3	1	4	.20		.06		
619.2	624.8	82207	5.6	5.6	2C0	2.99	.08	.19	.22	5.91			3	4	7	.22		.04		
624.8	630.3	82208	5.5	5.5	2L12	2.84	.04	.42	.69	9.02			2	1	4	.27		.04		
630.3	635.8	82209	5.5	5.4	2D0	3.25	.19	3.48	4.14	81.49			7	8	15	.09		.10		
635.8	641.3	82210	5.5	5.5	2L12	2.90	.08	.58	.12	18.35			4	3	8	.22		.06		

DDH: 82F-11 UTM-N: 8094.9 UTM-E: 14491.6 UTM-ELEV: 4009.4 TOTAL DEPTH: 603.6 SECTION: 124
RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----						-----ASSAYS-----																	
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.		
496.6	500.8	82225	4.2	4.2	2A4	3.00	.10	1.39	4.28	13.38		.07	4	7	12	.07		.05					
500.8	505.0	82226	4.2	4.2	2A4	3.19	.08	3.11	7.43	25.51		.55	2	5	7	.10		.01					
505.0	510.0	82227	5.0	5.0	2E4	4.44	.20	5.70	5.85	79.32		.14	4	21	26	4.25		.15					
510.0	515.0	82228	5.0	5.0	2E4	4.74	.11	5.74	6.61	96.11		.14	5	18	23	8.59		.21					
515.0	519.5	82229	4.5	4.5	2H4	4.12	.35	4.89	5.87	90.20		.07	16	12	28	4.56		.25					
519.5	524.0	82230	4.5	4.5	2H0	4.53	.49	2.96	5.00	46.66		.04	33	5	38	.07		.11					
524.0	528.0	82231	4.0	4.0	2D0	3.03	.13	2.70	4.35	50.08		.04	6	5	12	.13		.09					
528.0	532.1	82232	4.1	4.1	2D0	2.95	.08	1.24	2.97	25.19		.04	3	3	7	.19		.05					
532.1	536.2	82233	4.1	4.1	2D0	3.02	.12	1.93	3.53	33.90		.04	4	4	9	.14		.05					
536.2	539.6	82234	3.4	3.4	2A4	2.79	.12	1.20	3.25	24.88		.04	4	2	7	.34		.05					
539.6	543.0	82235	3.4	3.4	2A0	2.82	.09	1.17	2.32	23.33		.04	3	2	5	.44		.02					
543.0	547.0	82236	4.0	4.0	2B45	2.80	.08	1.20	2.61	21.46		.04	4	3	7	.34		.04					
547.0	550.9	82237	3.9	3.9	2B45	3.00	.15	1.52	3.33	47.90		.04	5	3	8	.32		.03					
550.9	555.8	82238	4.9	4.4	2A0	2.78	.05	.96	1.76	19.28		.04	2	3	5	.26		.03					
555.8	560.7	82239	4.9	4.0	2A0	2.74	.05	1.37	1.50	31.42		.07	2	2	5	.44		.03					
560.7	565.6	82240	4.9	4.9	2A0	2.84	.06	1.12	1.39	25.19		.14	2	2	5	.36		.03					
565.6	570.5	82241	4.9	4.8	2A0	2.73	.03	1.09	2.48	15.24		.14	2		3	.36		.02					
570.5	575.5	82242	5.0	3.7	2A4	2.79	.03	1.22	3.27	15.24		.14	2		3	.50		.03					

DDH: 82F-13 UTM-N: 7870.9 UTM-E: 14270.2 UTM-ELEV: 3946.6 TOTAL DEPTH: 641.0 SECTION: 124
RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS---		-----ASSAYS-----																		
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
559.5	565.3	82250	5.8	5.8	2A01	2.83	.08	.66	2.28	17.73		.07	4	2	7	.17		.04		
565.3	571.0	82251	5.7	5.4	2A01	2.78	.02	.87	2.25	17.73		.04	3	1	4	.32		.03		
571.0	575.6	82252	4.6	4.3	2B4	2.93	.03	1.95	3.62	36.08		.04	4	3	7	.23		.03		
575.6	580.1	82253	4.5	4.3	2B0	2.76	.02	.97	2.01	19.60		.04	2	1	3	.14		.01		
580.1	584.6	82254	4.5	4.1	2B0	2.79	.04	.66	2.50	17.11		.04	3	1	4	.16		.01		
584.6	588.0	82255	3.4	3.4	2D47	3.40	.21	4.16	8.31	89.89		.04	11	4	15	.20		.05		
588.0	591.4	82256	3.4	3.2	2D07	2.96	.38	2.18	4.10	49.77		.04	4	5	9	.19		.02		

DDH: 82F-15 UTM-N: 7087.1 UTM-E: 14693.1 UTM-ELEV: 4025.6 TOTAL DEPTH: 740.0 SECTION: 130
RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----		-----ASSAYS-----																		
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
590.3	595.5	82274	5.2	5.0	2LHA*	3.39	.51	.45	.52	23.02		10	11	21	.11		.03			
595.5	598.4	82275	2.9	2.8	2D0	3.28	.13	2.39	7.46	26.44	.41	2	11	13	.07		.05			
598.4	601.2	82276	2.8	2.8	2A1	2.28	.09	2.03	5.78	28.93	.07	1	7	8	.16		.01			
601.2	605.2	82277	4.0	3.8	2E4	4.81	.16	4.34	4.86	60.65	.17	5	27	32	.96		.19			
605.2	609.3	82278	4.1	4.1	2E4	3.16	.11	4.08	5.27	64.99	.10	5	26	31	3.99		.14			
609.3	610.2	82279	.9	.9	2H2	4.22	.54	4.99	6.26	97.04	.17	19	10	29	4.65		.35			
610.2	615.4	82280	5.2	5.2	2A4	2.22	.09	2.18	4.85	31.42	.07	6	1	7	.47		.05			
615.4	620.6	82281	5.2	5.2	2A4	3.00	.12	1.85	3.62	32.04	.04	4	3	8	.30		.03			
620.6	625.7	82282	5.1	4.7	2A0	2.93	.11	.94	1.78	27.99	.07	4	4	8	.55		.03			
625.7	630.8	82283	5.1	5.1	2A4	2.28	.09	1.46	4.29	31.42	.04	6	3	9	.26		.04			
630.8	635.9	82284	5.1	4.8	2A0	2.86	.07	.91	1.84	19.91	.07	4	2	7	.32		.02			
635.9	641.0	82285	5.1	5.1	2A0	2.23	.07	.98	2.53	24.26	.04	6	1	7	.35		.03			
641.0	646.1	82286	5.1	5.1	2A4	2.99	.09	1.70	4.22	32.66	.07	9	1	11	.37		.04			
646.1	651.2	82287	5.1	5.1	2A0	2.15	.08	.50	.93	15.24	.04	3	2	6	.49		.05			
672.0	676.5	82288	4.5	4.5	2A1	2.25	.07	.88	1.86	14.00	.04	5	4	9	.24		.06			
676.5	681.0	82289	4.5	4.1	2A41	2.62	.18	2.71	6.50	53.50	.07	10	13	23	.12		.03			

DDH: 82F-16 UTM-N: 7390.8 UTM-E: 14399.0 UTM-ELEV: 4004.4 TOTAL DEPTH: 707.0 SECTION: 127
RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
631.0	635.1	82290	4.1	4.1	2A0	2.17	.08	.47	.65	9.64			4	3	8	.17		.08			
635.1	639.2	82291	4.1	3.6	2A0	2.73	.05	.15	.19	7.15			2	3	5	.51		.17			
639.2	643.3	82292	4.1	4.1	2A4	2.79	.06	1.44	2.70	37.32		.41	2	3	5	.19		.03			
643.3	645.5	82293	2.2	2.2	2G4	4.15	.05	3.35	7.37	48.43		.17	2	12	15	20.77		.09			
645.5	649.6	82294	4.1	4.1	2E4	4.06	.29	5.68	8.11	89.58		.07	12	17	29	.68		.20			
649.6	653.7	82295	4.1	4.1	2E4	4.32	.15	5.82	8.36	87.40		.04	6	20	27	.20		.23			
653.7	657.8	82296	4.1	4.1	2E4	4.36	.20	7.36	7.38	111.35		.07	7	21	29	.30		.18			
657.8	662.0	82297	4.2	4.2	2A4	2.77	.06	1.50	3.21	27.68		.34	2	4	6	.15		.01			
662.0	666.3	82298	4.3	4.3	2A0	2.77	.02	.63	1.62	12.44		.14	1	2	4	.14		.01			
666.3	670.6	82299	4.3	4.3	2A0	2.81	.05	1.26	2.54	30.79		.21	3	3	7	.45		.01			
670.6	676.4	82300	5.8	5.7	2A47	3.80	.36	3.15	6.34	79.00		.04	30		30	.06		.04			
676.4	682.0	82301	5.6	5.6	2A0	2.74	.05	.60	1.23	16.17			3	2	5	.15		.03			

DDH: 82F-17 UTM-N: 7695.4 UTM-E: 14898.2 UTM-ELEV: 3912.9 TOTAL DEPTH: 400.0 SECTION: 128
RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----							-----ASSAYS-----													
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
298.8	301.0	82302	2.2	2.2	2A0	2.81	.15	.03	.10	7.47			3	2	6	.53				.04
301.0	305.5	82303	4.5	4.5	2D5	3.33	.20	2.03	6.69	23.64		.21	6	12	18	.05				.09
305.5	310.0	82304	4.5	4.5	2D5	3.37	.08	5.03	10.16	38.26		.21	4	8	13	.09				.05
310.0	315.6	82305	5.6	5.6	2E42	4.44	.16	5.09	4.61	71.54		.07	9	19	29	.06				.24
315.6	321.2	82306	5.6	4.4	2E42	4.48	.31	5.05	5.24	97.36		.04	16	13	29	.10				.39
321.2	326.8	82307	5.6	5.6	2E42	4.45	.18	2.65	3.88	40.44		.04	9	20	29	.03				.15
326.8	331.0	82308	4.2	4.2	2A41	2.98	.17	1.28	4.54	22.71		.07	5	3	8	.18				.05
331.0	335.1	82309	4.1	4.1	2A1	2.79	.12	.93	1.93	18.04		.01	3	2	5	.45				.02
335.1	339.2	82310	4.1	3.8	2A1	2.61	.03	.29	1.29	7.15			1		2	.68				.01
339.2	344.2	82311	5.0	5.0	2A0	2.80	.06	.08	.32	4.98			3	3	7	.53				.03
344.2	349.2	82312	5.0	5.0	2A0	2.79	.14	.08	.89	9.02			6		7	.30				.07
349.2	354.2	82313	5.0	5.0	2A0	2.85	.13	1.42	.99	31.10			5	2	8	.32				.05

DDH: 82F-22 UTM-N: 5158.4 UTM-E: 14959.7 UTM-ELEV: 4022.5 TOTAL DEPTH: 377.0 SECTION:
RFE: RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
324.8	328.8	82314	4.0	3.5	2C5	2.91	.08	.16	.85	14.93			7	1	8	.75		.04			
328.8	330.5	82315	1.7	1.7	2E41	3.41	.16	2.44	6.42	42.61			8	9	17	.14		.04			
330.5	333.2	82316	2.7	2.7	2C0	3.10	.13	1.49	6.07	34.84			6	2	9	.20		.03			
333.2	335.5	82317	2.3	2.3	2E0	3.47	.16	1.85	5.04	39.81			7	10	17	.57		.02			
335.5	340.5	82318	5.0	4.0	2A0	2.75	.09	.16	.55	16.17			3	2	5	.26		.01			
342.2	343.4	82319	1.2	1.2	2E41	3.68	.21	1.40	7.20	96.42			11	12	23	.21		.03			
343.4	347.2	82320	3.8	2.8	2D0	3.19	.09	1.31	6.56	38.59			6	5	11	.27		.02			
347.2	351.2	82321	4.0	2.8	2C0	2.19	.12	.22	.45	13.69			2		3	.14		.02			

DDH: 82F-24 UTM-N: 6646.4 UTM-E: 15322.0 UTM-ELEV: 4007.4 TOTAL DEPTH: 127.0 SECTION: 135
RFE: S2 RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----		-----ASSAYS-----																		
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
32.0	35.5	82322	3.5 2.0	2E46	5.00	1.05	5.99	.82	102.02		.69		26	26	5.10		.02			
35.5	39.0	82323	3.5 1.8	2E46	4.54	.35	7.63	4.02	131.57		.55	1	20	21	6.73		.12			
39.0	45.0	82324	6.0 .8	2D06	3.08	.68	2.69	3.91	54.12		.17	1	5	6	3.87		.08			
45.0	48.0	82325	3.0 .2	2G0	3.20	.20	.28	4.57	15.24		.04	1	3	4	23.71		.10			
48.0	54.0	82326	6.0 2.3	2C0	2.87	.35	3.32	4.25	35.77		.07	1		2	2.43		.04			
54.0	60.0	82327	6.0 5.1	2A4	4.10	.14	4.41	5.23	55.99		.21	1	1	3	1.44		.02			
60.0	65.0	82328	5.0 5.0	2A4	2.86	.12	1.81	3.04	30.79		.07		3	4	.34		.01			
65.0	70.0	82329	5.0 5.0	2A4	2.92	.13	1.76	3.50	27.68		.07	1	3	4	2.83		.03			
70.0	75.5	82330	5.5 5.0	2A4	2.78	.10	3.53	1.22	53.19		.21		1	2	.60		.01			
82.0	87.0	82331	5.0 3.8	2A0	2.65	.08	.71	1.33	25.19		.07	8	1	9	.81		.04			
87.0	90.0	82332	3.0 3.0	2A0	2.67	.08	.66	.99	18.04			1	2	3	.52		.01			
90.0	94.5	82333	4.5 4.5	2A0	2.17	.03	.66	1.16	16.17			1	2	3	.49		.04			

DDH: 83F-01 UTM-N: 6783.0 UTM-E: 14782.1 UTM-ELEV: 4035.5 TOTAL DEPTH: 656.5 SECTION: 132+00E
RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
568.0	569.2	82350	1.2	1.0	2E4	3.02	.12	2.43	4.27	30.17		.14	5	6	11	.20		.10			
569.2	575.0	82351	5.8	5.8	2A0	2.68	.03	.69	1.70	14.00		.13	1		1	.36		.02			
575.0	580.1	82352	5.1	5.1	2A0	2.74	.06	.79	1.15	22.08		.29	2	1	3	.29		.07			
580.1	584.3	82353	4.2	3.4	2A4	2.70	.05	3.14	3.56	65.94		.41	2	1	3	.28		.05			
584.3	586.9	82354	2.6	2.5	2L0	2.74	.07	.16	.26	6.53		.02	3	3	7	.94		.14			

DDH: 83F-02 UTM-N: 6577.2 UTM-E: 14564.5 UTM-ELEV: 4023.0 TOTAL DEPTH: 893.0 SECTION: 132+00E
RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

---DEPTHS---						---ASSAYS---																
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.	
721.6	723.7	82355	2.1	2.1	2A3	3.10	.20	.35	1.70	11.20		.33	7	8	16	.20		.04				
723.7	726.3	82356	2.6	2.6	2A4	3.00	.14	2.18	4.50	38.88		.21	4	5	10	.19		.02				
726.3	728.3	82357	2.0	2.0	2A0	2.80	.05	1.26	1.85	42.30		.90	1		2	.68		.02				
728.3	730.4	82358	2.1	2.1	2H46	4.20	.21	5.32	8.12	88.33		.16	17	10	28	5.98		.14				
730.4	737.0	82359	6.6	6.6	2E64	4.10	.10	4.29	6.78	61.90		.09	5	17	22	4.94		.10				
737.0	738.4	82360	1.4	1.4	2Q4&	3.52	.38	4.88	3.11	87.40		.22	6	10	17	3.33		.11				
738.4	739.9	82361	1.5	1.3	2E46	4.46	.08	5.83	6.64	92.69		.11	4	22	26	5.85		.22				
739.9	743.0	82362	3.1	3.1	2D6	3.29	.10	2.92	4.72	42.61		.12	3	9	12	5.25		.06				
743.0	745.7	82363	2.7	2.6	2D64	3.52	.19	6.09	4.54	111.04		.38	4	11	15	12.05		.09				
745.7	749.9	82364	4.2	4.2	2G4	4.51	.22	4.64	5.80	67.81		.12	5	19	24	12.15		.22				
749.9	751.6	82365	1.7	1.7	2D36	4.15	.24	3.25	4.27	56.92		.17	5	16	22	15.74		.28				
751.6	755.6	82366	4.0	4.0	2G4	4.58	.22	4.72	4.99	84.91		.21	6	21	27	6.36		.27				
755.6	759.3	82367	3.7	3.4	2G4	4.67	.17	5.56	6.31	94.87		.18	6	19	26	8.98		.26				
759.3	762.6	82368	3.3	3.3	2E41	4.23	.09	4.91	8.67	55.36		.20	5	20	26	.22		.07				
762.6	764.4	82369	1.8	1.7	2D5	3.01	.08	1.69	5.93	17.11		.20	3	3	7	.27		.06				
764.4	769.4	82370	5.0	4.9	2A41	2.87	.13	1.03	2.89	21.15		.20	3	4	8	.24		.03				
769.4	773.2	82371	3.8	3.8	2A41	2.79	.07	1.40	3.25	20.53		.19	3	2	6	.40		.06				
773.2	778.0	82372	4.8	4.6	2A41	2.76	.03	1.08	2.89	13.38		.20	1	3	5	.35		.03				
778.0	782.7	82373	4.7	4.7	2A41	2.78	.04	.96	2.61	17.11		.21	1	6	7	.31		.04				
782.7	787.0	82374	4.3	4.3	2A0	2.76	.02	.74	1.88	12.13		.19	1	1	2	.40		.01				
787.0	791.9	82375	4.9	4.3	2A0	2.66	.02	1.30	2.46	23.02		.13	2		3	.27		.04				

DDH: 83F-04 UTM-N: 6357.4 UTM-E: 14356.4 UTM-ELEV: 4016.9 TOTAL DEPTH: 800.7 SECTION: 132+00E
RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
696.6	699.2	82376	2.6	2.6	1D4	2.81	.02	.33	.60	3.11		.05	2	2	4	.33		.07			
699.2	703.2	82377	4.0	4.0	2A4	2.94	.05	1.34	3.05	23.95		.20	1	5	6	.22		.03			
703.2	707.6	82378	4.4	4.4	2E41	3.61	.09	1.86	4.80	45.10		.21	2	19	22	.19		.04			
707.6	710.5	82379	2.9	2.9	2E4	3.90	.14	5.47	8.83	95.49		.09	7	16	24	.19		.15			
710.5	712.3	82380	1.8	1.6	2D0	2.88	.07	2.09	2.98	46.66		.12	3	3	6	.36		.03			
712.3	716.4	82381	4.1	4.0	2D5	2.87	.06	1.04	2.64	35.77		.15	3	4	7	.27		.04			
716.4	720.1	82382	3.7	3.7	2A14	2.82	.06	2.45	2.47	66.87		.26	5	2	7	.32		.06			
720.1	723.8	82383	3.7	3.7	2A14	2.79	.06	1.39	2.89	40.12		.24	2	2	5	.27		.03			
775.0	777.0	82384	2.0	2.0	2D0	2.89	.07	1.29	3.57	44.79		.01	7	1	9	.34		.09			
789.6	790.8	82385	1.2	1.2	0Q9	2.86	.05	.09	.17	5.29		.03	4	4	9	.38		.07			
792.8	793.5	82386	.7	.7	0Q9	2.92	.04	.12	.16	6.22		.01	7	3	10	.43		.09			
794.5	795.6	82387	1.1	1.1	0Q9	2.96	.05	.03	.07	4.98		.01	5	4	10	.29		.08			

DDH: 83F-07 UTM-N: 6641.7 UTM-E: 15201.5 UTM-ELEV: 4013.7 TOTAL DEPTH: 202.0 SECTION: 132+100E
RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----						-----ASSAYS-----																	
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.		
52.0	61.0	82388	9.0	2.3	2G4	4.41	.21	5.23	5.80	83.05		.19	3	19	23	13.13		.22					
61.0	64.5	82389	3.5	.7	2G4	4.23	.21	4.69	5.81	58.16		.12	4	18	23	14.34		.28					
64.5	68.0	82390	3.5	3.5	2A41	2.78	.08	1.50	3.35	22.08		.07		2	2	.56		.01					
68.0	72.0	82391	4.0	4.0	2A41	2.80	.13	2.10	4.00	28.62		.07	1	3	4	.73		.02					
72.0	76.0	82392	4.0	3.8	2A41	2.73	.07	2.28	4.05	25.19		.10	1	1	2	.66		.01					
76.0	80.0	82393	4.0	3.2	2A41	2.74	.09	1.27	3.67	14.93		.10	2	2	4	.35		.02					
80.0	87.0	82394	7.0	2.2	2A41	2.72	.22	2.51	6.51	28.62		.19	2	1	3	.32		.05					
87.0	90.4	82395	3.4	3.4	2A41	2.67	.08	1.27	4.01	18.35		.11	2	2	4	.56		.02					
90.4	97.0	82396	6.6	6.6	2A1	2.65	.05	.56	1.18	12.75		.08	2	1	3	.53		.01					

DDH: 83F-08 UTM-N: 6125.0 UTM-E: 14587.4 UTM-ELEV: 4021.7 TOTAL DEPTH: 690.0 SECTION: 132+300E
RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

---DEPTHS---						---ASSAYS---															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
632.6	636.4	82397	3.8	3.8	2A41	2.74	.05	1.03	3.08	13.69		.09	2	4	6	.25			.06		
636.4	641.5	82398	5.1	5.1	2E4	3.87	.16	4.63	6.89	80.56		.13	6	14	21	7.01			.14		
641.5	645.5	82399	4.0	4.0	2A4&	2.70	.02	.65	1.68	12.75		.51	1	1	3	.29			.03		
645.5	648.2	82400	2.7	2.7	2D0	3.28	.07	3.28	6.85	53.81		.18	4	9	14	.32			.05		
648.2	652.0	82401	3.8	3.7	2A1	2.72	.04	1.33	2.23	26.44		.13	2	2	4	.29			.03		
652.0	655.0	82402	3.0	3.0	2A1	2.70	.02	.69	1.70	19.60		.51	1	1	3	.26			.03		

DDH: 83F-09 UTM-N: 6645.6 UTM-E: 15039.6 UTM-ELEV: 4013.1 TOTAL DEPTH: 493.0 SECTION: 132+300E
RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

										-----ASSAYS-----											
-----DEPTHS---		SAMPLE	INT.	REC.	ROCK	S.G.	Cu	Pb	Zn	Ag(AA)	Ag(FA)	Au(FA)	Po	Py	TOT	BaO	Hg	Mn	As	Ba	S.G.
FROM	TO	NO.			UNIT	PULP	%	%	%	g/mT	g/mT	g/mT	%	%	Fe	%	%	%	%	%	W.R.
238.4	240.6	82403	2.2	2.1	2A0	2.79	.05	.25	.41	11.82		.11	5	3	8	.19		.17			

DDH: 83F-10 UTM-N: 5689.5 UTM-E: 14541.0 UTM-ELEV: 3981.1 TOTAL DEPTH: 727.0 SECTION: 132+600E
RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

---DEPTHS---						ASSAYS															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
352.1	355.3	82404	3.2	3.2	2L0&	2.82	.04	.35	.35	8.71		.02	2	3	5	.27		.06			
355.3	359.3	82405	4.0	4.0	2A0	2.79	.09	.74	1.79	18.05		.21	2	4	6	.19		.03			
359.3	364.9	82406	5.6	5.6	2A0&	2.82	.05	.65	2.36	17.11		.15	1	3	4	.20		.01			
364.9	370.5	82407	5.6	5.6	2A0&	2.77	.03	1.02	2.61	12.75		.25	1	3	4	.22		.01			
370.5	375.8	82408	5.3	5.2	2A0	2.75	.03	.98	2.48	23.02		.23	1	3	4	.26		.01			
375.8	381.0	82409	5.2	5.2	2A0	2.80	.02	.92	2.29	23.01		.16	1	4	6	.23		.01			
381.0	386.7	82410	5.7	5.7	2A0	2.69	.02	.44	.74	12.13		.11	1	1	2	.88		.03			
386.7	392.4	82411	5.7	5.6	2A0	2.66	.02	.47	.85	8.71		.14		1	2	.87		.01			
392.4	395.7	82412	3.3	3.3	2A0	2.79	.05	.53	1.19	5.60		.19	1	4	6	.75		.02			
395.7	399.1	82413	3.4	3.4	2A0	2.72	.02	.26	.38	3.11		.04	2	1	4	.73		.04			

DDH: 83F-12 UTM-N: 6860.6 UTM-E: 14280.4 UTM-ELEV: 4004.7 TOTAL DEPTH: 832.0 SECTION: 127+300E
RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
736.6	738.6	82431	2.0	2.0	2H41	3.89	.19	5.12	8.79	82.11		.14	13	14	28	.40		.13			
738.6	742.2	82432	3.6	3.4	2E41	4.22	.11	5.50	9.53	81.49		.13	7	22	29	.18		.11			
742.2	744.2	82433	2.0	2.0	2E4&	3.96	.11	4.66	8.69	74.65		.13	4	21	26	.43		.09			
744.2	748.0	82434	3.8	3.5	2E4	4.25	.17	4.37	8.05	65.01		.12	7	23	30	.59		.27			
748.0	752.2	82435	4.2	4.2	2E4	3.87	.14	3.94	7.63	62.52		.25	6	19	25	.27		.13			
752.2	755.5	82436	3.3	3.3	2A34	3.19	.05	2.20	5.96	32.66		.41	3	10	14	.32		.04			
755.5	760.0	82437	4.5	3.1	2A34	2.94	.11	2.03	3.41	52.25		.65	4	4	9	.32		.04			
760.0	764.7	82438	4.7	4.2	2A34	2.79	.13	1.26	3.15	37.64		1.60	3	12	15	.26		.03			

DDH: 83F-14 UTM-N: 6750.3 UTM-E: 15309.6 UTM-ELEV: 3985.5 TOTAL DEPTH: 198.5 SECTION: 132+400E
RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
9.7	15.0	82439	5.3	.9	2A0?	2.62	.01	.20	.37	9.64		.05				.56		.01			
15.0	22.0	82440	7.0	.7	2A0?	2.60	.01	.25	.16	8.71		.03				.48		.01			
22.0	26.0	82441	4.0	.4	2A0?	2.60	.06	.38	.40	8.09		.05			1	.66		.01			
26.0	30.0	82442	4.0	.4	2A0	2.60	.05	.51	.41	15.24		.14		1	1	.29		.01			
30.0	34.0	82443	4.0	1.4	2A0	2.69	.11	.58	1.33	15.86		.12		1	2	.42		.01			
34.0	38.2	82444	4.2	1.4	2A0	2.67	.11	.88	1.93	21.46		.10			1	.59		.02			
38.2	40.3	82445	2.1	2.1	2A1	2.67	.03	.37	.42	11.20		.05	2	1	4	.50		.02			
40.3	42.0	82446	1.7	1.7	2A11	2.83	.02	.31	.91	6.84		.29	4	2	6	.22		.16			
96.5	98.1	82447	1.6	1.4	0Q9	2.85	.12	.30	.63	17.73		.01	3	5	8	.19		.03			
98.1	102.8	82448	4.7	3.8	2A0	2.67	.04	.41	1.29	14.93		.05	1	1	2	.55		.03			
102.8	107.4	82449	4.6	4.6	2A0	2.70	.04	.37	.78	16.80		.47	1	1	2	.77		.03			
107.4	108.5	82450	1.1	1.1	0Q9	3.27	.10	12.03	.26	660.33		.07	2	7	10	.24		.03			

DDH: 83F-15 UTM-N: 7078.3 UTM-E: 14504.0 UTM-ELEV: 4013.0 TOTAL DEPTH: 759.0 SECTION: 127+300E
RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

---DEPTHS---						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
641.4	647.0	82451	5.6	5.6	2A4	2.94	.11	2.36	3.95	29.24		.27	3	3	7	.20		.02			
647.0	652.7	82452	5.7	5.5	2D0	2.90	.10	3.88	2.08	50.08		.55	3	2	5	.32		.02			
652.7	654.8	82453	2.1	2.0	2E46	4.33	.03	4.34	12.32	59.41		.14	2	24	27	4.60		.05			
654.8	660.6	82454	5.8	5.6	2G41	4.28	.12	4.55	7.50	74.65		.09	5	16	22	14.17		.20			
660.6	662.3	82455	1.7	1.7	2D4	3.72	.17	4.78	5.08	67.50		.19	9	9	18	10.53		.15			
662.3	666.5	82456	4.2	4.1	2F46	3.84	.19	4.49	6.85	87.10		.23	9	16	25	4.03		.16			
666.5	669.8	82457	3.3	3.3	2E4&	4.51	.10	2.48	5.96	48.21		.10	7	28	36	.19		.05			
669.8	675.2	82458	5.4	5.3	2A41	3.03	.05	1.74	4.41	24.37		.12	4	3	7	.36		.02			
675.2	680.5	82459	5.3	5.1	2A41	2.81	.06	1.07	2.88	21.15		.14	3	2	6	.27		.01			
680.5	684.0	82460	3.5	3.4	2A3&	2.90	.10	1.06	2.51	29.55		.27	2	5	7	.25		.01			
684.0	687.4	82461	3.4	3.4	2A0	2.82	.05	.53	1.75	9.95		.05	3	2	5	.24		.01			
687.4	689.4	82462	2.0	2.0	2A1	2.75	.06	.52	1.55	15.55		.08	3		3	.22		.02			
689.4	692.6	82463	3.2	3.1	2D5	2.87	.05	.97	2.73	24.26		.04	5	2	8	.28		.04			
692.6	695.7	82464	3.1	3.1	2D5	3.09	.14	1.60	3.50	34.34		.05	8	6	14	.35		.03			
695.7	700.0	82465	4.3	4.0	2A1	2.79	.05	.80	2.02	17.42		.04	2	2	4	.21		.01			
700.0	704.3	82466	4.3	4.1	2A1	2.82	.06	.91	2.04	29.55		.05	3	2	6	.20		.04			
704.3	708.6	82467	4.3	4.3	2A1	2.78	.03	.66	2.08	15.55		.04	2	1	3	.34		.02			
708.6	709.7	82468	1.1	1.1	2C0	2.85	.05	.62	.77	18.35		.05	3	3	7	.26		.13			

DDH: 83F-16 UTM-N: 6713.9 UTM-E: 15410.5 UTM-ELEV: 3984.9 TOTAL DEPTH: 196.0 SECTION: 132+500E
RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----		-----ASSAYS-----																		
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
15.0	20.0	82469	5.0	5.0	2A0	2.67	.14	1.28	.54	15.55	.02			1	.77					
20.0	21.4	82470	1.4	1.4	2A0	2.69	.18	1.44	1.25	12.75	.01		1	1	.79					
21.4	25.0	82471	3.6	3.6	2A1	2.71	.12	1.30	1.44	12.13	.02	1	1	3	.72		.01			
25.0	28.9	82472	3.9	3.9	2L4	2.68	.13	.68	.47	8.71	.01	3		4	.77		.02			
28.9	33.8	82473	4.9	4.9	2A1	2.73	.11	.48	.73	10.25	.02	2	2	5	.87		.01			
33.8	37.5	82474	3.7	3.7	2A0	2.71	.04	.61	.63	9.02	.04	1	2	3	.60		.03			
37.5	39.0	82475	1.5	1.5	2A4	2.86	.05	.74	1.09	8.09	.02	3	3	6	.35		.11			
39.0	44.0	82476	5.0	5.0	2L4	2.75	.02	.40	.84	5.60	.04	3		4	.56		.09			
68.0	72.0	82477	4.0	3.4	2A0	2.78	.04	.62	.68	9.64	.02	4	1	5	.67		.09			
72.0	77.0	82478	5.0	5.0	2A0	2.77	.04	.76	1.91	14.31	.12	2	1	4	.72		.03			
77.0	81.5	82479	4.5	4.4	2A0	2.80	.04	.64	1.95	18.04	.10	3	2	5	.75		.03			
81.5	86.0	82480	4.5	4.3	2D5	2.94	.05	1.68	3.10	35.77	.09	4	3	8	.53		.05			
86.0	90.0	82481	4.0	3.4	2A1	2.82	.04	.93	2.13	16.49	.07	3	1	5	.66		.04			
90.0	95.0	82482	5.0	5.0	2D5	2.88	.07	1.18	2.54	18.66	.14	3	3	7	.34		.05			
95.0	100.6	82483	5.6	5.4	2L4	2.88	.05	.97	2.42	18.35	.01	5	3	9	.39		.08			
100.6	102.7	82484	2.1	2.0	2A0	2.82	.06	.29	.74	6.84	.01	3	3	7	.29		.04			
109.2	109.8	82485	.6	.6	2E34	3.50	.08	3.64	6.54	73.72	.05	5	18	23	.19		.17			

DDH: 83F-17 UTM-N: 6650.4 UTM-E: 15501.8 UTM-ELEV: 3986.9 TOTAL DEPTH: 200.0 SECTION: 132+600E
RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

---DEPTHS---						---ASSAYS---															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
9.5	12.0	82486	2.5	2.5	2A0	2.66	.03	1.01	.12	21.77		.03				1.04		.01			
12.0	15.0	82487	3.0	3.0	2A0	2.64	.02	.80	.08	10.26		.03				1.03					
15.0	19.0	82488	4.0	4.0	2A0	2.61	.02	.63	.12	12.44		.05				1.37					
19.0	24.0	82489	5.0	5.0	2A0	2.62	.05	.56	.10	9.95		.07				1.13					
24.0	29.0	82490	5.0	5.0	2A0	2.67	.07	.73	.45	15.86		.04			1	1.02					
29.0	31.8	82491	2.8	2.8	2A0	2.70	.05	.49	.50	7.78		.03			1	.70					

DDH: 83F-19 UTM-N: 7346.4 UTM-E: 14193.2 UTM-ELEV: 3988.6 TOTAL DEPTH: 787.0 SECTION: 122+600E
RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	ASSAYS													
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %
694.5	697.9	82513	3.4	3.4	2A41	2.74	.04	.85	2.51	20.84		.05	5	3	8	.25		.05		
697.9	699.5	82514	1.6	1.6	2D4	3.23	.11	4.84	7.16	68.12		.05	9	6	16	.20		.08		
699.5	704.1	82515	4.6	4.6	2E41	3.66	.18	6.47	10.64	96.11		.09	14	9	24	.18		.14		
704.1	708.7	82516	4.6	4.6	2E41	3.38	.09	8.57	16.20	114.15		.09	10	3	14	.14		.15		
708.7	713.2	82517	4.5	4.0	2E46	3.51	.12	7.51	13.90	101.71		.07	12	5	18	1.35		.16		
713.2	717.5	82518	4.3	4.3	2H41	3.87	.22	5.96	11.00	90.82		.07	21	7	28	1.65		.15		
717.5	721.8	82519	4.3	4.3	2H41	3.72	.26	4.00	8.97	66.56		.08	24	7	31	.61		.11		
721.8	726.0	82520	4.2	4.2	2H41	3.63	.20	5.13	10.16	78.38		.12	20	6	26	.81		.08		
726.0	728.0	82521	2.0	1.4	2E41	3.83	.06	4.08	7.81	45.10		.12	5	21	26	.20		.05		
728.0	732.7	82522	4.7	4.3	2A43	2.82	.07	1.06	2.70	21.46		.22	3	5	9	.21		.02		
732.7	735.9	82523	3.2	3.2	2A0	2.76	.07	.64	1.46	16.80		.11	4	2	6	.22		.02		

DDH: 83F-20 UTM-N: 6482.3 UTM-E: 15145.2 UTM-ELEV: 4005.4 TOTAL DEPTH: 197.0 SECTION: 132+500E
RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS----				-----ASSAYS-----																
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
116.5	122.0	82524	5.5	5.5	2A0	2.79	.04	.72	1.45	15.24		.10	3	1	4	.36		.11		

DDH: 83F-22 UTM-N: 7143.7 UTM-E: 13992.6 UTM-ELEV: 3989.6 TOTAL DEPTH: 917.0 SECTION: 122+600
RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----		-----ASSAYS-----																		
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
834.4	838.0	33501	3.6	3.3	2A41	2.87	.03	2.16	2.94	27.37		.10	4	3	7	.14		.05		
838.0	842.4	33502	4.4	3.4	2A1	2.93	.06	1.16	2.77	25.82		.10	4	4	8	.18		.03		
842.4	843.0	33503	.6	.6	2D4	3.45	.11	6.96	11.03	118.82		.10	8	5	13	.09		.09		
843.0	845.3	33504	2.3	2.0	2H41	3.91	.20	4.65	7.85	94.24		.10	20	6	26	.20		.09		
845.3	846.3	33505	1.0	1.0	2A41	3.17	.06	2.57	4.46	37.95		.10	10	3	13	.28		.06		
846.3	848.9	33506	2.6	2.5	2F4&	4.41	.09	3.50	7.70	46.66		.10	10	21	32	.10		.03		
848.9	851.8	33507	2.9	2.9	2D05	2.99	.06	1.58	3.51	25.50		.10	4	2	7	.25		.02		
851.8	855.4	33508	3.6	3.6	2A1&	2.85	.05	.80	2.26	17.42		.20	4	2	6	.14		.02		
855.4	860.0	33509	4.6	4.6	2A1&	2.81	.04	1.03	2.41	18.66		.20	3	3	6	.11		.02		
860.0	865.1	33510	5.1	4.9	2A1&	2.99	.07	.97	2.79	23.64		.30	3	4	7	.16		.02		
865.1	868.1	33511	3.0	3.0	2Q0	3.05	.13	1.65	2.58	53.19		.80	5	4	10	.14		.03		

DDH: 84F-02 UTM-N: 7557.8 UTM-E: 13989.6 UTM-ELEV: 3985.5 TOTAL DEPTH: 855.0 SECTION: 122+300E
RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
778.9	781.0	33550	2.1	2.1	2L12	2.88	.03	.17	.24	5.60		.10	2	2	4	.24		.06			
781.0	786.7	33551	5.7	5.7	2A4	3.00	.05	1.28	2.73	26.44		.10	3	2	5	.14		.03			
786.7	789.8	33552	3.1	2.7	2D0	3.33	.15	2.42	4.42	41.37		.10	9	8	17	.15		.05			
789.8	790.5	33553	.7	.7	2E43	3.84	.17	3.13	5.64	58.47		.10	13	16	29	.04		.07			
790.5	793.0	33554	2.5	2.4	2D0	3.15	.13	3.58	4.84	51.32		.10	5	4	10	.15		.03			
793.0	797.0	33555	4.0	4.0	2A4	2.99	.08	1.23	3.15	15.24		.10	5	5	10	.20		.03			
797.0	801.6	33556	4.6	4.0	2A4	2.98	.05	1.79	3.10	22.39		.10	4	3	8	.16		.01			
801.6	804.0	33557	2.4	2.4	2A0	2.90	.08	.95	2.57	21.46		.10	4	3	7	.17		.02			
804.0	809.0	33558	5.0	4.6	1D49	2.73	.02	.06	.14	2.49		.10	5		5	.22		.05			

DDH: 84F-03 UTM-N: 9277.7 UTM-E: 14732.1 UTM-ELEV: 3791.7 TOTAL DEPTH: 381.0 SECTION: 119+000
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	---ASSAYS---													
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %
154.9	161.7	33559	6.8	6.6	2E14	3.70	.22	2.32	3.53	47.59		.10	12	14	26	3.96		.10		
174.8	179.0	33560	4.2	4.2	2D39	3.54	.22	2.03	5.00	46.34		.10	11	10	22	3.29		.16		
179.0	184.3	33561	5.3	4.2	2L2	3.17	.18	1.64	1.42	37.95		.10	8	9	17	4.90		.14		
184.3	189.3	33562	5.0	4.9	2E49	4.23	.30	4.56	3.67	97.36		.20	12	21	34	1.07		.26		
189.3	191.4	33563	2.1	2.1	2E4	4.70	.17	3.99	4.52	51.01		.20	2	33	35	.13		.05		
191.4	196.0	33564	4.6	4.5	2E4&	4.32	.15	1.92	2.51	22.39		.10	4	30	35	.04		.14		
196.0	200.0	33565	4.0	3.9	2E09	4.58	.39	1.92	2.69	38.26		.10	8	30	38	.03		.25		
200.0	203.6	33566	3.6	3.5	2E09	4.45	.25	1.86	1.79	29.86		.10	7	29	37	.08		.24		
203.6	206.7	33567	3.1	2.6	2E41	4.54	.17	6.65	6.13	76.20		.20	2	29	31	.09		.06		
206.7	212.0	33568	5.3	2.6	2E0&	4.62	.26	1.97	2.18	22.08		.10	3	34	37	1.01		.10		
212.0	216.0	33569	4.0	4.0	2E0&	4.49	.21	1.19	2.65	16.80		.10	3	31	35	.03		.10		
216.0	220.4	33570	4.4	4.4	2E4	4.42	.17	2.14	4.23	20.84		.10	2	31	34	.43		.08		
220.4	225.7	33571	5.3	5.3	2E89	4.41	.28	.57	1.02	3.42		.10	9	29	39	.01		.35		
225.7	230.0	33572	4.3	4.3	2E09	4.59	.40	.30	1.16	4.66		.10	5	33	39	.01		.16		
230.0	235.0	33573	5.0	5.0	2E4	4.45	.17	2.22	3.46	18.04		.10	3	31	34	.01		.06		
235.0	240.4	33574	5.4	5.4	2E49	4.55	.20	3.18	6.12	18.97		.10	4	31	36	.02		.12		
240.4	242.7	33575	2.3	2.1	2F49	4.53	.22	7.85	13.32	30.48		.10	7	23	31	.02		.42		
242.7	247.9	33576	5.2	5.2	2E1	4.21	.13	.31	1.33	10.26		.10	2	31	34	.02		.03		
247.9	250.4	33577	2.5	2.5	2E1	3.84	.12	.13	.84	10.89		.10	2	26	29	.01		.04		
250.4	252.7	33599	2.3	2.0	2E4	4.28	.19	3.11	8.48	13.06		.10	6	23	29	.01		.29		
252.7	257.4	33578	4.7	4.7	2E89	4.03	.63	.62	2.68	11.20		.10	7	28	35	.01		.24		
257.4	262.0	33579	4.6	4.6	2E89	4.58	.63	.48	1.80	14.31		.10	7	31	38	.01		.22		
262.0	264.5	33580	2.5	2.5	2E89	4.33	.48	.44	2.26	7.15		.10	9	29	38	.01		.30		
264.5	269.1	33581	4.6	4.6	2E4	4.68	.09	4.99	9.15	26.75		.40	2	31	33	.01		.03		
269.1	272.0	33582	2.9	2.9	2D35	3.46	.11	1.16	4.95	14.00		.10	2	16	18	.07		.03		
272.0	274.7	33583	2.7	2.7	2A1	2.96	.08	.54	1.49	16.48		.20	2	8	10	.20		.03		
274.7	278.0	33584	3.3	3.2	2D0&	2.95	.08	3.68	5.51	35.46		.10	3	2	5	.18		.04		
278.0	281.3	33585	3.3	3.2	2C0&	2.41	.21	.49	1.84	14.93		.20	4	8	12	.20		.02		
281.3	286.7	33586	5.4	5.0	2C37	3.94	.55	1.46	3.26	22.39		.10	19	14	33	.10		.03		
286.7	289.4	33587	2.7	2.7	2C5	3.59	.06	.20	1.17	5.91		.10	1	23	24	.03		.01		
289.4	291.9	33588	2.5	2.5	2D5	3.56	.14	2.28	4.91	35.15		.10	1	20	21	.04		.02		
291.9	295.8	33589	3.9	3.7	2C5	3.29	.09	1.11	.74	17.73		.10	1	18	20	.03		.02		
295.8	299.0	33590	3.2	3.2	2D4	3.42	.08	7.39	20.60	25.50		.20	4	4	8	.16		.02		
299.0	305.0	33591	6.0	6.0	2D4	3.38	.09	6.78	17.70	41.99		.10	4	6	10	.11		.08		
305.0	307.0	33592	2.0	2.0	2C0	3.15	.19	.58	1.94	9.02		.10	6	9	15	.15		.04		
307.0	309.0	33593	2.0	1.9	2A1	2.89	.11	1.00	1.74	21.15		.10	3	3	7	.25		.02		
309.0	314.0	33594	5.0	5.0	2A41	2.89	.07	2.80	4.24	38.26		.60	2	3	5	.18		.02	.15	
314.0	318.7	33595	4.7	4.7	2A41	2.76	.06	1.52	4.87	23.64		.40	1	1	3	.21		.02	.09	
318.7	324.0	33596	5.3	5.3	2A41	2.85	.06	1.51	3.18	27.37		.60	1	2	4	.17		.01	.14	
324.0	329.5	33597	5.5	5.5	2A1	2.79	.09	.67	2.05	15.24		.20	2	3	5	.18		.01		
329.5	333.8	33598	4.3	4.1	2A41	2.76	.07	1.75	4.76	19.91		.10	2	1	4	.17		.06		

DDH: 84F-04 UTM-N: 7355.1 UTM-E: 13783.6 UTM-ELEV: 3960.3 TOTAL DEPTH: 923.0 SECTION: 122+300E
RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %
840.9	847.9	33729	7.0	7.0	2A0&	3.00	.05	1.34	3.72	21.15		.10	4	2	6	.17		.05		
847.9	850.1	33730	2.2	2.2	1F4@	2.97	.06	1.24	4.26	22.08		.10	8	3	12	.58		.05		
850.1	851.8	33731	1.7	1.7	2E43	3.58	.10	4.80	12.60	75.58		.10	12	7	19	1.04		.12		
851.8	854.0	33732	2.2	2.1	1F@	2.80	.05	.25	.33	5.91		.10	4	2	7	1.00		.06		
854.0	856.9	33733	2.9	2.9	2B4	2.86	.03	1.26	3.14	21.46		.10	2	1	4	.47		.02		
856.9	860.0	33734	3.1	2.8	2A14	3.02	.05	1.60	3.33	29.24		.30	4	1	6	.38		.02		
860.0	862.8	33735	2.8	2.8	2B4	2.96	.07	3.01	4.83	86.78		.80	4	2	7	.21		.04		
862.8	864.4	33736	1.6	1.6	1F4@	3.13	.11	5.21	6.43	139.97		.30	9	3	13	.11		.08		
864.4	865.9	33737	1.5	1.2	2E43	3.93	.22	6.47	8.63	206.53		.40	9	16	26	.02		.10		
865.9	868.8	33738	2.9	2.7	1F4@	2.97	.06	.80	1.81	19.91		.10	10	1	12	.16		.06		
868.8	872.2	33739	3.4	3.4	2E34	3.75	.22	1.98	3.38	49.45		.10	13	17	30	.10		.08		
872.2	875.5	33740	3.3	3.3	0Q0	2.90	.06	.11	.20	3.42		.10	3	2	6	.18		.04		
875.5	877.7	33741	2.2	2.1	2A0	2.82	.05	.85	1.66	22.39		.30	3	3	6	.13		.02		
877.7	880.1	33742	2.4	1.6	2C0	2.91	.07	.56	1.13	10.57		.30	3	3	6	.10		.03		

DDH: 84F-05 UTM-N: 9442.8 UTM-E: 14851.5 UTM-ELEV: 3776.6 TOTAL DEPTH: 460.0 SECTION: 119+000
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	ASSAYS															
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.	
24.0	29.8	33641	5.8	5.6	2D43	3.75	.12	3.52	6.78	69.36		.80	3	16	20	8.66		.05				
29.8	33.8	33642	4.0	4.0	2L0	2.84	.07	.36	.17	8.09		1.60	4	1	5	.69		.03				
33.8	36.5	33643	2.7	2.7	2D43	3.49	.26	4.42	10.78	101.90		.40	5	12	17	.13		.06				
36.5	40.0	33644	3.5	3.5	2H49	4.21	.56	4.25	6.97	126.90		.20	34	3	38	.03		.03				
40.0	42.8	33645	2.8	2.8	2D43	3.50	.24	4.50	9.48	125.66		.60	6	10	17	.30		.06				
69.4	74.7	33646	5.3	5.3	2D3	3.45	.12	1.98	6.29	17.11		.10	3	14	18	.90		.09				
74.7	78.7	33647	4.0	4.0	2E08	4.58	.13	1.73	2.30	18.97		.10	1	35	36	3.30		.01				
78.7	79.9	33648	1.2	1.2	2F4	4.45	.05	9.27	16.90	75.27		.10	3	23	26	.06		.03				
79.9	83.0	33649	3.1	3.0	2E49	4.75	.23	1.73	2.52	17.42		.10	1	38	39	.02		.02				
83.0	86.7	33650	3.7	3.6	2E0	4.77	.19	1.30	1.22	17.11		.10	1	39	40	.07		.01				
86.7	90.6	33651	3.9	3.9	2E09	4.44	.34	.16	.29	10.57		.10	1	37	39	.03		.02				
90.6	94.2	33652	3.6	3.4	2D35	3.24	.12	1.50	4.78	31.42		.80	1	14	15	.14		.03				
94.2	98.0	33653	3.8	3.7	2E09	4.46	.34	.15	.37	9.95		.10	1	37	39	.01		.03				
98.0	101.8	33654	3.8	3.8	2E09	4.16	.23	.14	.68	5.29		1.00	2	33	36	.02		.07				
101.8	105.0	33655	3.2	3.2	2E08	4.13	.24	1.51	1.73	8.40		.10	7	28	35	.03		.26				
105.0	110.0	33656	5.0	5.0	2E48	4.36	.25	1.62	3.00	8.09		.10	9	28	37	.02		.22				
110.0	115.0	33657	5.0	5.0	2E48	4.02	.35	1.90	3.09	12.13		.10	12	27	39	.07		.28				
115.0	120.0	33658	5.0	5.0	2E08	3.68	.48	1.26	.72	34.84		1.00	7	19	27	.62		.19				
120.0	125.7	33659	5.7	5.6	2E08	3.59	.26	.09	1.41	2.80		.10	6	28	34	.11		.10				
125.7	128.8	33660	3.1	3.1	2E09	4.45	.35	.04	.47	3.73		.10	1	37	39	.02		.03				
128.8	131.7	33661	2.9	2.9	2E1	4.04	.13	.14	.74	5.29		.10	1	31	32	.04		.02				
131.7	133.5	33662	1.8	1.7	2E41	3.90	.11	5.96	6.44	21.77		.20	2	23	26	.03		.02				
133.5	137.3	33663	3.8	3.8	2E0	3.62	.12	.28	.44	6.84		.20	2	27	30	.09		.02				
137.3	141.0	33664	3.7	3.6	2D39	3.45	.28	3.26	5.11	68.74		2.00	2	15	17	.07		.05				
141.0	145.0	33665	4.0	4.0	2C3	3.59	.12	.27	.20	16.48		.40	1	23	25	.03		.01				
145.0	150.1	33666	5.1	5.1	2C3	3.48	.11	1.89	1.08	74.03		.40	1	19	21	.04		.05				
150.1	154.2	33667	4.1	4.1	2D45	3.42	.09	3.26	7.82	29.86		.80	1	14	16	.08		.03				
154.2	158.0	33668	3.8	3.8	2C3	3.57	.06	.45	.90	7.46		.20		24	24	.06		.01				
158.0	162.3	33669	4.3	4.1	2C39	3.91	.20	.18	1.03	2.49		.10	3	27	30			.11				
162.3	166.3	33670	4.0	4.0	2E09	3.80	.20	.37	2.04	4.04		.10	6	22	29			.17				
166.3	171.3	33671	5.0	5.0	2E49	3.91	.20	2.19	3.47	4.04		.10	8	20	28	.01		.22				
171.3	173.8	33672	2.5	2.5	2E81	4.09	.20	.47	2.13	3.11		.10	8	34	42			.22				
173.8	180.0	33673	6.2	5.7	2E81	4.03	.25	.40	1.38	3.42		.10	7	33	40	.02		.18				
180.0	185.0	33674	5.0	4.9	2E89	4.20	.61	.09	1.12	2.49		.10	10	25	35			.27				
185.0	190.0	33675	5.0	5.0	2E89	4.41	.31	.15	2.01	4.04		.10	11	26	38			.33				
190.0	195.0	33676	5.0	5.0	2E19	4.08	.53	.67	.58	9.64		.10	4	26	31	.01		.15				
195.0	200.0	33677	5.0	5.0	2E89	4.37	.78	1.01	2.31	10.88		.10	9	36	45			.30				
200.0	205.0	33678	5.0	4.8	2E89	4.02	.66	1.00	.99	20.22		.30	3	27	30	.01		.09				
205.0	209.0	33679	4.0	4.0	2E89	4.47	.39	.10	.98	10.57		.10	6	31	38	.01		.22				
209.0	215.0	33680	6.0	5.8	2E09	4.25	.58	.14	.95	14.62		.10	1	33	34	.02		.04				
215.0	220.0	33681	5.0	5.0	2E09	4.44	.52	.88	2.22	14.00		.10	2	31	34	.01		.07				
220.0	225.0	33682	5.0	5.0	2E08	4.26	.17	.15	1.49	7.15		.10	2	32	34	.01		.07				
225.0	230.0	33683	5.0	5.0	2E08	4.27	.17	.14	1.98	6.22		.10	2	31	33	.01		.08				
230.0	235.0	33684	5.0	5.0	2C3	4.07	.08	1.18	3.95	10.89		.10	1	28	30	.01		.04				
235.0	239.0	33685	4.0	4.0	2C3	3.96	.04	.77	1.96	8.71		.10	1	28	29	.03		.03				
239.0	243.2	33686	4.2	4.1	2C3	3.96	.04	1.07	.56	8.09		.10		29	29	.03		.02				
243.2	248.0	33687	4.8	4.8	2D43	3.49	.06	3.42	8.23	23.02		.10	2	17	20	.06		.03				
248.0	252.0	33688	4.0	3.7	2D43	3.57	.05	3.58	10.79	26.13		.10	2	17	20	.04		.03				
252.0	255.3	33689	3.3	3.2	2E4	4.49	.03	3.00	6.55	25.50		.10	1	32	33	.01		.03				
255.3	258.0	33690	2.7	2.7	2D0	3.13	.12	1.48	2.63	15.86		.10	6	6	12	.23		.03				

DDH: 84F-05 UTM-N: 9442.8 UTM-E: 14851.5 UTM-ELEV: 3776.6 TOTAL DEPTH: 460.0 SECTION: 119+000
RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %
258.0	261.7	33691	3.7	3.4	2C0	2.93	.17	.26	.25	5.91		.20	3	5	9	.28		.02		
261.7	265.0	33692	3.3	3.0	2D5	2.95	.08	1.52	3.73	18.04		.30	2	4	6	.30		.03		
265.0	271.3	33693	6.3	6.3	2C35	3.29	.07	.74	2.16	18.04		.30	2	14	16	.14		.02		
271.3	275.0	33694	3.7	3.7	2C3	3.36	.05	.94	2.40	19.28		.40	2	15	17	.14		.02		
275.0	279.0	33695	4.0	4.0	2D3	3.14	.07	1.10	2.95	23.33		.30	3	7	11	.17		.03		
279.0	283.0	33696	4.0	4.0	2D0	2.96	.08	1.45	3.42	18.66		.30	4	4	8	.21		.04		
283.0	285.9	33697	2.9	2.8	2D0	2.99	.07	1.41	3.08	22.39		.30	3	5	9	.17		.04		
285.9	289.0	33698	3.1	3.1	2A13	3.14	.05	1.02	2.76	23.95		.30	1	11	13	.17		.02		
289.0	294.0	33699	5.0	4.6	2A13	3.03	.05	.28	.64	12.75		.30	1	9	11	.20		.02		
294.0	299.0	33700	5.0	4.6	2C0&	3.07	.07	.96	1.14	21.77		.10	3	8	11	.30		.03		
299.0	305.2	33701	6.2	6.2	2C0&	3.00		.74	1.82	18.35		.10	3	5	8	.23		.03		
305.2	309.0	33702	3.8	3.8	2D5	2.85	.07	1.56	3.80	20.22		.50	1	2	4	.25		.02		
309.0	314.0	33703	5.0	5.0	2A13	2.96	.06	.50	1.61	15.55		.10	1	6	8	.23		.02		
314.0	319.0	33704	5.0	5.0	2A13	3.00	.07	.16	.10	9.02		.10	3	7	11	.21		.02		
319.0	324.2	33705	5.2	5.2	2A13	2.97	.16	.13	.05	12.13		.10	5	7	12	.18		.02		
324.2	330.4	33706	6.2	6.2	2C7	3.13	.19	.58	.35	20.84		.10	11	6	17	.13		.02		
330.4	333.0	33707	2.6	2.5	2A13	2.97	.05	1.31	.05	13.37		.50	2	7	9	.21		.02		
333.0	336.0	33708	3.0	3.0	2A13	2.92	.05	.30	1.53	28.62		.30	2	9	11	.22		.02		
336.0	339.9	33709	3.9	3.9	2A13	2.87	.05	.22	1.88	9.02		.10	4	3	7	.20		.02		
339.9	344.5	33710	4.6	4.5	2C7	3.02	.15	.28	.87	19.60		.10	11	1	13	.18		.02		
344.5	349.0	33711	4.5	4.5	2C7	3.19	.19	.49	.28	12.44		.10	14	3	17	.17		.02		
349.0	353.3	33712	4.3	3.3	2C79	3.04	.22	.77	.12	15.55		.10	11		11	.13		.02		
353.3	359.0	33713	5.7	5.7	2C7&	2.98	.11	.22	.06	5.91		.10	11		11	.20		.02		
359.0	364.0	33714	5.0	5.0	2C7&	3.02	.16	.14	.04	4.98		.10	9	3	12	.18		.03		
364.0	369.6	33715	5.6	5.5	2C79	3.39	.29	.38	.23	10.57		.10	21		22	.13		.03		
369.6	372.8	33716	3.2	3.2	2C79	3.33	.29	.30	.58	10.57		.10	14	5	19	.16		.03		
372.8	376.0	33717	3.2	3.2	2D0	3.48	.16	3.83	4.65	60.03		.30	8	4	12	.13		.04		
376.0	378.5	33718	2.5	2.5	2D4	3.37	.13	6.90	8.81	102.95		.50	7	3	10	.06		.05		
378.5	383.3	33719	4.8	4.5	2L2	3.13	.08	2.72	.46	63.45		.10	6	2	8	.18		.04		
383.3	386.8	33720	3.5	3.5	2L2	2.85	.11	.23	.09	5.29		.10	6	4	10	.24		.04		
386.8	391.8	33721	5.0	5.0	2A1	2.84	.06	1.04	1.72	15.86		.10	3	2	5	.18		.04		
391.8	396.7	33722	4.9	4.8	2A14	2.82	.04	1.18	3.95	13.37		.10	3	2	5	.20		.04		
396.7	399.7	33723	3.0	2.7	0Q9	3.04	.12	12.65	.98	286.16		.80	3	2	6	.06		.04		
399.7	403.0	33724	3.3	3.3	2B09	3.05	.20	1.79	.58	39.81		.30	4	4	8	.11		.03		
403.0	407.0	33725	4.0	3.9	2D0&	2.80	.11	2.41	4.11	29.24		.10	4	3	7	.08		.03		
407.0	411.2	33726	4.2	4.2	2L2	2.89	.06	1.11	2.14	13.68		.10	2	1	3	.16		.07		
411.2	414.5	33727	3.3	3.3	2B4&	2.94	.08	2.17	2.82	26.75		.10	3	2	5	.10		.06		
414.5	417.0	33728	2.5	2.5	2B0&	2.82	.05	1.15	1.26	17.73		.10	3	1	5	.11		.05		

DDH: 84F-06 UTM-N: 9295.8 UTM-E: 14499.3 UTM-ELEV: 3690.4 TOTAL DEPTH: 301.0 SECTION: 118+000
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %
121.8	126.2	33743	4.4	4.4	2D43	3.36	.20	3.99	10.02	60.03		.10	7	8	16	.03		.14		
126.2	130.7	33744	4.5	4.2	2D03	3.60	.29	2.68	5.55	54.74		.10	9	14	24	.03		.19		
130.7	134.0	33745	3.3	1.3	2E48	4.29	.29	4.88	6.60	88.65		.10	13	19	33	.36		.38		
134.0	138.6	33746	4.6	4.0	2E0&	4.31	.38	1.95	1.62	35.15		.10	5	30	35	.07		.15		
138.6	143.6	33747	5.0	4.4	2E42	4.68	.26	4.06	4.09	54.43		.10	1	35	37	.02		.04		
143.6	148.4	33748	4.8	3.7	2E42	4.67	.31	3.65	3.36	32.04		.10	3	32	36	.01		.10		
148.4	152.0	33749	3.6	3.6	2E48	4.70	1.09	1.72	2.30	18.66		.10	6	31	38	.01		.20		
152.0	155.6	33750	3.6	3.6	2E48	4.76	.44	3.54	3.03	69.05		.10	11	27	39	.10		.29		
155.6	158.7	33751	3.1	3.1	2F4	5.02	.13	4.65	9.68	27.68		.10	2	30	33	.01		.07		
158.7	161.8	33752	3.1	2.8	2F4	4.65	.09	8.05	15.90	63.45		.10	3	24	27	.01		.06		
161.8	165.3	33753	3.5	3.4	2E0&	4.66	.26	2.94	4.03	33.28		.10	5	31	36			.17		
165.3	170.3	33754	5.0	5.0	2E0&	4.66	.26	1.91	2.45	23.02		.10	5	32	37	.01		.20		
170.3	175.3	33755	5.0	5.0	2E0&	4.64	.23	3.52	4.30	46.34		.10	5	30	35			.29		
175.3	177.9	33756	2.6	2.6	2F4	4.63	.08	14.00	22.00	122.55		.10	5	15	21	.06		.17		
177.9	179.8	33757	1.9	1.9	2E87	4.50	.31	5.01	4.97	89.58		.10	15	21	36	.08		.20		
179.8	179.9	90001	.1	.1	FUDGE	2.75														
179.9	180.9	33758	1.0	1.0	2K8	3.73	.11	1.82	1.47	23.33		.10	33	1	35	.06		.90		
180.9	184.0	33759	3.1	3.0	2E89	4.52	1.11	1.09	2.23	17.42		.10	7	30	37	.02		.19		
184.0	187.9	33760	3.9	3.9	2J88	4.30	.19	4.49	3.97	72.16		.10	39	3	43	.14		.16		
187.9	191.8	33761	3.9	3.9	2J88	4.32	.08	1.66	2.22	67.18		.10	46	3	49	.03		.15		
191.8	195.7	33762	3.9	3.9	2J88	4.40	.22	4.12	3.60	29.24		.10	40	3	44	.03		.17		
195.7	201.1	33763	5.4	5.4	2J88	4.18	.11	5.66	4.93	20.53		.10	41	1	42	.03		.17		
201.1	206.5	33764	5.4	5.2	2J88	4.30	.69	4.85	3.94	40.12		.10	33	6	39	.02		.23		
206.5	211.8	33765	5.3	5.2	2J88	4.11	.17	4.15	4.83	19.91		.10	35	4	39	.03		.21		
211.8	215.3	33766	3.5	3.5	2D49	3.15	.30	2.04	4.42	29.24		.10	5	6	12	.14		.09		
215.3	218.7	33767	3.4	3.4	2D4&	3.05	.13	2.75	6.11	32.97		.10	4	4	8	.27		.11		
218.7	221.8	33768	3.1	3.1	2A1	2.85	.10	.39	.98	9.64		.10	4	3	7	.13		.10		
252.2	255.1	33769	2.9	2.8	2Q0	2.96	.15	1.54	3.05	35.15		.10	4	5	9	.11		.06		
255.1	259.5	33770	4.4	4.4	2C79	3.24	.43	.31	.43	23.64		.30	12	8	21	.16		.06		
259.5	263.9	33771	4.4	4.4	2C79	2.81	.13	.23	.10	48.21		4.30	3	2	6	.28		.05		
285.0	289.8	33632	4.8	4.6	0Q9	2.78	.10	4.38	.10	41.99		.10	1	1	2	.06		.02		
289.8	294.6	33633	4.8	4.8	0Q9	3.01	.26	13.00	.10	202.49		5.00	1	1	2	.04		.03		

DDH: 84F-07 UTM-N: 6374.3 UTM-E: 14799.6 UTM-ELEV: 4009.2 TOTAL DEPTH: 626.0 SECTION: 132+300E
RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----						-----ASSAYS-----																
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.	
563.8	566.3	33636	2.5	2.5	2E49	3.89	.22	5.00	8.61	83.98		.20	9	16	25	.11		.16				
566.3	570.3	33637	4.0	4.0	2D0	3.04	.10	1.62	3.97	33.90		.10	4	5	10	.06		.07				
570.3	574.2	33638	3.9	3.9	2D0	3.14	.11	1.37	4.67	28.30		.10	6	7	13	.09		.07				
574.2	579.2	33639	5.0	4.7	2A0	2.85	.08	1.55	3.85	36.08		.20	3	3	7	.24		.04				
579.2	583.3	33640	4.1	4.0	2A0	2.85	.05	.80	1.86	20.53		.10	3	2	5	.21		.06				

DDH: 84F-08 UTM-N: 9597.3 UTM-E: 14999.4 UTM-ELEV: 3758.7 TOTAL DEPTH: 280.0 SECTION: 119+000
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

---DEPTHS---						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
43.2	49.2	33604	6.0	6.0	2C39	3.53	.21	.90	1.21	31.10		.60	5	18	23	.08		.06			
49.2	54.7	33605	5.5	5.5	2D3	3.69	.07	1.28	3.48	19.60		.40	1	22	24	.06		.01			
54.7	56.8	33606	2.1	2.1	2D43	3.51	.12	4.13	9.84	35.77		.20	6	10	17	.08		.10			
56.8	61.5	33607	4.7	4.7	2C37	3.18	.35	.80	1.53	13.37		.10	12	7	19	.07		.09			
90.2	92.5	33608	2.3	2.3	2E19	3.66	.23	.12	.51	7.78		.10	3	23	27	.02		.03			
92.5	97.5	33609	5.0	5.0	2D3	3.36	.14	1.57	4.17	17.73		.10	3	14	18	.07		.03			
97.5	102.5	33610	5.0	5.0	2D3	3.19	.11	2.68	5.57	23.02		.10	3	11	15	.06		.03			
102.5	107.5	33611	5.0	5.0	2A43	3.36	.06	5.19	8.62	46.97		.40	2	13	15	.08		.01			
107.5	112.5	33612	5.0	4.6	2A43	3.33	.07	2.61	5.86	29.24		.20	2	14	16	.07		.02			
112.5	117.5	33613	5.0	4.7	2A43	3.35	.07	2.95	7.56	34.52		.40	1	14	16	.06		.01			
117.5	122.5	33614	5.0	5.0	2A43	3.60	.05	1.66	5.43	23.33		.10	1	19	21	.09		.01			
122.5	128.3	33615	5.8	5.3	2A43	3.38	.05	1.85	5.44	21.46		.10	2	14	16	.11		.01			
128.3	131.2	33616	2.9	2.9	2D35	3.46	.03	2.40	7.09	26.75		.20	1	15	17	.10		.01			
131.2	137.6	33617	6.4	6.4	2A43	3.37	.04	2.48	5.73	27.68		.40	1	15	17	.09		.01			
137.6	140.7	33618	3.1	3.1	2A3	3.15	.05	.53	2.15	11.20		.10	1	15	16	.13		.01			
140.7	146.7	33619	6.0	6.0	2D35	3.34	.08	1.11	3.29	17.11		.10	2	18	21	.09		.02			
146.7	152.0	33620	5.3	5.3	2D35	3.22	.08	.93	4.57	19.28		.10	4	11	15	.15		.02			
152.0	157.0	33621	5.0	5.0	2A13	3.01	.06	.23	.61	14.93		.10	4	11	15	.11		.04			
157.0	162.0	33622	5.0	5.0	2A41	3.36	.06	1.42	3.63	27.06		.20	2	14	16	.08		.02			
162.0	168.1	33623	6.1	6.1	2A41	3.27	.05	1.69	4.89	27.68		.10	2	13	15	.11		.02			
168.1	172.0	33624	3.9	3.7	2A13	3.07	.08	.29	.31	14.00		.10	5	9	14	.15		.01			
172.0	175.2	33625	3.2	3.2	2A13	3.09	.04	.33	1.54	13.37		.10	1	13	14	.13		.01			
175.2	180.2	33626	5.0	5.0	2C0	3.29	.13	.52	1.14	13.06		.10	5	12	17	.05		.02			
180.2	185.6	33627	5.4	5.4	2C0	3.51	.11	.24	1.76	9.95		.10	9	13	22	.11		.01			
185.6	190.2	33628	4.6	4.6	2C5	3.56	.06	.30	1.40	11.82		.20	7	18	25	.10		.01			
190.2	195.2	33629	5.0	5.0	2A13	3.04	.08	.40	1.37	13.06		.10	3	10	14	.20		.01			
195.2	200.2	33630	5.0	5.0	2A13	3.18	.07	.67	1.05	18.35		.20	3	14	18	.11		.01			
200.2	204.6	33631	4.4	4.4	2A13	3.16	.09	.24	1.71	12.13		.20	5	13	18	.16		.01			
204.6	209.0	33634	4.4	4.4	2H9	4.10	.33	1.08	4.90	24.26		.10	35	3	39	.01		.02			
209.0	214.1	33635	5.1	5.1	2D09	3.09	.21	1.51	3.93	27.37		.20	6	5	12	.16		.02			

DDH: 84F-09 UTM-N: 6504.6 UTM-E: 14501.2 UTM-ELEV: 4020.6 TOTAL DEPTH: 814.0 SECTION: 132+000E
RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
747.1	751.0	33772	3.9	3.8	2D4	3.36	.13	5.14	9.20	116.64		.40	7	7	14	.09		.12			
751.0	753.9	33773	2.9	2.9	2A1	2.79	.15	.39	.87	9.33		.10	4	4	8	.21		.04			
753.9	756.3	33774	2.4	2.4	2D09	3.37	.22	2.94	5.83	50.70		.30	7	11	18	.08		.10			
756.3	759.6	33775	3.3	3.3	2D0	2.89	.09	4.08	3.41	74.96		.30	3	3	6	.22		.05			
759.6	763.0	33776	3.4	3.4	2B0	2.69	.06	.76	1.67	16.48		.10	2	1	3	.30		.03			
763.0	767.7	33777	4.7	4.7	2A41	2.99	.08	5.22	3.69	110.73		.50	2	2	5	.24		.05			
767.7	772.5	33778	4.8	4.8	2A41	2.74	.05	1.15	2.86	21.15		.10	2	1	3	.15		.04			

DDH: 84F-10 UTM-N: 7362.1 UTM-E: 14790.8 UTM-ELEV: 3886.3 TOTAL DEPTH: 525.0 SECTION: 127+300E
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	ASSAYS													
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %
400.9	403.0	33779	2.1	2.0	2D49	3.18	.38	4.47	6.80	60.96		.30	5	9	14	.10		.12		
403.0	405.8	33780	2.8	2.7	2G48	4.62	.49	4.54	5.40	67.50		.10	10	22	33	4.15		.29		
405.8	409.5	33781	3.7	3.6	2F49	4.72	.22	4.68	5.97	64.07		.10	5	26	31	.10		.19		
409.5	412.7	33782	3.2	3.2	2G4	4.35	.18	5.16	5.92	82.11		.10	8	18	26	6.88		.27		
412.7	415.9	33783	3.2	3.1	2G4	4.61	.11	4.80	5.10	93.93		.10	6	23	30	4.41		.32		
415.9	417.3	33784	1.4	1.4	2G47	4.37	.22	5.01	5.99	87.71		.10	11	17	28	5.14		.26		
417.3	422.0	33785	4.7	4.4	2D0	3.11	.11	1.42	4.49	25.19		.10	3	5	8	.20		.06		
422.0	426.7	33786	4.7	4.7	2D0	2.95	.08	1.85	4.53	30.17		.10	3	3	7	.11		.06		
426.7	430.9	33787	4.2	3.8	2A1&	2.88	.05	.78	1.80	15.55		.10	2	2	4	.30		.03		
430.9	435.1	33788	4.2	3.9	2A1&	2.91	.06	1.24	2.28	23.64		.10	2	4	7	.29		.04		
435.1	438.5	33789	3.4	3.4	2B5	2.88	.08	.88	1.86	25.82		.10	4	3	7	.22		.04		
438.5	442.0	33790	3.5	3.0	2D5	3.00	.08	1.85	3.48	33.59		.10	3	3	6	.23		.04		
442.0	447.2	33791	5.2	3.4	2A41	3.12	.09	3.27	4.03	69.98		.10	6	5	11	.20		.09		
447.2	451.5	33792	4.3	3.9	2A0	2.75	.05	.64	1.72	12.44		.10	2	1	3	.54		.03		
451.5	454.8	33793	3.3	2.0	2B5	2.82	.07	.97	2.00	19.91		.10	2	2	4	.36		.03		
454.8	458.2	33794	3.4	3.4	2B45	2.98	.07	3.96	2.07	90.51		.10	2	3	5	.31		.04		
458.2	463.9	33795	5.7	5.6	2A03	2.89	.10	1.97	1.13	27.99		.10	3	4	8	.17		.12		
463.9	469.5	33796	5.6	5.3	2A03	2.79	.05	.13	.22	2.49		.10	2	2	5	.40		.16		
469.5	475.2	33797	5.7	5.7	2A03	2.84	.10	.64	.41	43.55		.40	2	2	4	.36		.10		

DDH: 84F-13 UTM-N: 7054.9 UTM-E: 15127.6 UTM-ELEV: 3872.5 TOTAL DEPTH: 210.0 SECTION: 132+052E
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

---DEPTHS---							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
71.1	74.4	33810	3.3	3.3	2D0	3.21	.18	1.10	4.51	19.91		.26	3	8	12	.31		.05			
74.4	79.9	33811	5.5	5.3	2D0	3.63	.14	4.09	5.33	62.83		.11	6	13	20	.34		.19			
79.9	84.6	33812	4.7	4.6	2A1	2.91	.07	.98	1.71	21.15		.03	2	3	5	.69		.03			
84.6	89.6	33813	5.0	5.0	2D3&	3.17	.08	2.02	5.63	44.48		.04	4	4	8	.18		.04			
89.6	95.0	33814	5.4	5.4	2A41	3.09	.08	1.13	5.07	23.33		.07	4	4	8	.37		.03			
95.0	99.3	33815	4.3	4.1	2A41	2.90	.05	.83	2.97	18.66		.11	3	2	5	.51		.03			
99.3	104.3	33816	5.0	5.0	2A0	2.86	.04	1.26	2.67	22.71		.13	2	1	4	.82		.03			
104.3	108.0	33817	3.7	3.7	2B0	2.73	.05	.38	1.00	9.33		.03	2	2	4	.79		.02			
108.0	110.4	33818	2.4	2.4	2B0	2.80	.07	.43	.84	12.75		.13	2	3	5	.68		.02			
110.4	115.4	33819	5.0	2.2	2B0	2.80	.06	.75	2.27	18.35		.08	2	3	5	.63		.02			
115.4	120.4	33820	5.0	2.7	2D0	3.00	.09	1.51	5.39	27.68		.07	5	5	10	.30		.05			
120.4	124.9	33821	4.5	4.5	2D0	2.80	.08	2.12	3.56	41.06		.05	3	2	6	.43		.04			
124.9	129.0	33822	4.1	4.0	1E19	2.60	.05	.49	1.29	10.58		.05	2	2	4	.57		.10			
174.1	179.7	33823	5.6	5.5	0Q9	3.17	.32	2.68	4.79	93.62		.07	7	7	14	.15		.06			
179.7	183.5	33824	3.8	3.4	2L14	2.80	.28	.97	2.36	47.28		.50	6	1	7	.27		.05			

DDH: 84F-14 UTM-N: 7186.1 UTM-E: 15019.7 UTM-ELEV: 3870.6 TOTAL DEPTH: 335.0 SECTION: 131+022E
RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----				-----ASSAYS-----																
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
228.5	231.5	33825	3.0	2.8	2A1	3.24	.18	1.44	3.14	37.32	.05	8	8	17	.42		.05			

DDH: 84F-18 UTM-N: 8715.3 UTM-E: 14518.6 UTM-ELEV: 3915.6 TOTAL DEPTH: 585.0 SECTION: 121+000
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

-----DEPTHS-----		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----															
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.	
379.9	383.2	33826	3.3	3.3	2C39	3.33	.57	.61	.18	21.27		.31	6	13	20	.22		.04				
383.2	386.0	33827	2.8	2.6	2D39	3.17	.26	2.00	5.83	41.68		1.20	5	6	12	.18		.05				
386.0	389.6	33828	3.6	3.5	2D39	3.41	.39	1.54	8.85	29.55		.45	13	4	17	.63		.15				
389.6	391.0	33829	1.4	1.4	2H41	4.13	.50	4.75	7.46	74.03		.19	24	7	31	.30		.32				
391.0	396.0	33830	5.0	5.0	2E46	4.68	.05	4.61	6.79	64.07		.20	2	28	31	3.09		.29				
396.0	400.0	33831	4.0	4.0	2G4	4.64	.16	4.63	5.64	55.37		.22	2	23	26	8.55		.27				
400.0	405.4	33832	5.4	5.4	2G4	4.65	.14	5.24	6.07	90.82		.27	7	18	25	11.48		.37				
405.4	409.5	33833	4.1	4.1	2H49	4.30	.30	5.11	7.46	65.63		.09	20	10	30	.54		.27				
420.4	424.0	33834	3.6	3.6	2H43	4.28	.29	5.62	8.42	71.85		.07	18	11	30	.70		.20				
424.0	426.9	33835	2.9	2.9	2H43	4.44	.28	6.03	7.34	91.45		.08	14	17	32	.76		.20				
426.9	432.0	33836	5.1	5.0	2H43	4.45	.31	5.03	6.69	76.20		.13	35	1	37	2.31		.19				
432.0	437.0	33837	5.0	5.0	2H43	4.41	.31	5.96	7.62	93.31		.06	23	9	33	2.32		.20				
437.0	441.0	33838	4.0	4.0	2K43	4.20	.27	4.09	5.15	59.41		.05	17	14	32	.26		.14				
441.0	444.0	33839	3.0	3.0	2K43	4.16	.29	4.53	6.18	65.32		.05	17	12	30	.20		.12				
444.0	447.8	33840	3.8	3.6	2H43	4.39	.30	5.96	9.11	86.16		.06	25	5	30	.28		.11				
447.8	450.5	33841	2.7	2.7	2G4	4.59	.11	4.18	5.81	59.72		.05	5	19	24	13.49		.08				
450.5	453.6	33842	3.1	3.1	2G4	4.68	.14	4.19	5.98	40.12		.04	1	18	20	20.69		.05				
453.6	457.4	33843	3.8	3.8	2E09	4.89	.31	1.35	.76	16.49		.03	1	36	37	.52		.02				
457.4	461.0	33844	3.6	3.6	2E46	4.74	.46	3.27	4.93	32.35		.04	1	25	27	10.07		.03				
461.0	464.8	33845	3.8	3.6	2E46	4.73	.22	2.11	3.19	143.08		.05	2	31	33	3.54		.03				
464.8	468.0	33846	3.2	3.2	2G49	4.73	.20	5.95	7.28	51.94		.04	2	21	23	10.46		.05				
468.0	471.5	33847	3.5	3.5	2G4	4.71	.13	4.84	7.12	56.30		.08	2	12	14	26.72		.06				
471.5	477.2	33848	5.7	5.7	2E46	4.71	.24	3.01	3.32	33.28		.04	3	30	34	1.15		.06				
477.2	483.3	33849	6.1	6.1	2E49	4.65	.23	2.74	4.90	30.48		.05	3	30	33	.29		.08				
483.3	488.3	33850	5.0	5.0	2E09	4.52	.54	1.72	1.69	42.30		.15	5	30	35	.17		.20				
488.3	492.6	33851	4.3	3.7	2E09	4.59	.90	1.53	1.27	35.46		.10	3	23	27	.15		.17				
492.6	495.0	33852	2.4	2.4	2E09	4.49	.26	1.84	1.90	25.82		.06	4	25	30	.15		.19				
495.0	501.0	33853	6.0	6.0	2E4	4.55	.19	4.19	6.12	37.01		.03	3	28	31	.15		.05				
501.0	506.4	33854	5.4	5.4	2E4	4.76	.09	4.96	9.70	39.19		.03	2	28	30	.15		.02				
506.4	512.0	33855	5.6	5.6	2E49	4.79	.37	3.07	4.43	32.97		.03	2	32	34	.15		.04				
512.0	517.0	33856	5.0	4.7	2E4	4.80	.18	2.15	4.58	34.53		.05	4	31	35	.16		.04				
517.0	520.4	33857	3.4	3.4	2E4	4.81	.11	2.32	4.81	28.30		.10	3	32	35	.15		.06				
520.4	523.1	33858	2.7	2.6	2D09	3.21	.27	2.81	4.01	62.21		.09	4	7	11	.30		.03				
523.1	528.4	33859	5.3	5.1	2D39	3.13	.21	1.37	2.83	28.93		.07	4	8	12	.35		.03				
528.4	533.5	33860	5.1	5.1	2D39	3.02	.13	1.44	5.22	37.32		.21	4	6	10	.31		.03				
533.5	539.4	33861	5.9	5.9	2A0	2.81	.27	1.15	2.05	33.28		.11	3	2	5	.26		.04				

DDH: 84F-19 UTM-N: 8896.6 UTM-E: 14700.0 UTM-ELEV: 3913.8 TOTAL DEPTH: 597.0 SECTION: 121+000
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	---ASSAYS---													
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %
339.3	340.4	33862	1.1	1.1	1E19	2.75	.07	.11	.18	6.84		.05	3	2	5	.50		.04		
340.4	345.5	33863	5.1	5.0	2E19	3.48	.41	.09	.26	14.62		.14	6	16	23	.21		.09		
345.5	348.6	33864	3.1	3.1	2D43	3.58	.09	1.95	14.10	35.77		.15	4	12	17	.24		.10		
348.6	351.6	33865	3.0	3.0	2H46	4.35	.28	4.55	7.04	76.83		.13	18	11	30	5.73		.23		
351.6	357.4	33866	5.8	5.8	2H46	4.14	.28	4.90	8.79	81.18		.11	21	8	30	3.00		.29		
357.4	359.9	33867	2.5	2.5	2G07	4.40	.25	3.09	5.40	57.54		.07	24	2	27	18.47		.15		
359.9	362.0	33868	2.1	2.0	2H69	4.30	.32	3.36	6.24	67.81		.13	39		39	1.19		.20		
362.0	366.6	33869	4.6	4.4	2L14	3.30	.10	3.35	3.27	68.12		.05	8	6	15	3.85		.14		
366.6	370.8	33870	4.2	4.2	2L14	2.77	.04	.32	.46	11.82		.11	4	3	8	3.24		.07		
370.8	375.8	33871	5.0	5.0	2L14	2.73	.04	.12	.27	7.78		.10	4	3	7	2.25		.06		
375.8	378.5	33872	2.7	2.7	2E41	3.86	.09	3.58	9.08	57.85		.07	7	16	23	2.64		.13		
378.5	380.8	33873	2.3	2.3	2H43	4.38	.25	5.82	9.97	86.16		.08	27	9	36	.30		.12		
380.8	384.0	33874	3.2	3.0	2G47	4.34	.16	4.50	8.98	59.41		.10	13	9	22	21.12		.10		
384.0	386.2	33875	2.2	2.2	2K47	3.99	.19	7.52	12.00	103.58		.09	15	12	27	1.47		.15		
386.2	390.0	33876	3.8	3.8	2L14	2.98	.07	.73	.97	13.69		.06	4	4	9	5.61		.04		
390.0	391.8	33877	1.8	1.8	2Q96	3.90	.13	4.62	8.80	99.53		.09	10	16	26	2.94		.21		
391.8	393.9	33878	2.1	2.1	2H06	2.96	.12	.87	1.12	17.11		.02	4	3	7	4.41		.03		
393.9	398.6	33879	4.7	4.7	2H49	4.14	.31	5.33	7.78	98.60		.07	29	9	38	1.03		.30		
398.6	400.0	33880	1.4	1.4	1H4	2.92	.14	1.12	1.95	18.97		.03	9	6	15	3.39		.18		
400.0	402.0	33881	2.0	2.0	2E4*	4.26	.20	7.33	9.39	129.08		.09	12	14	27	5.36		.39		
402.0	403.0	33882	1.0	1.0	1H4	2.91	.08	1.54	1.04	21.15		.03	10		11	2.56		.15		
403.0	406.5	33883	3.5	3.5	2E46	4.09	.25	4.47	12.00	85.23		.09	15	12	28	4.05		.40		
406.5	408.4	33884	1.9	1.8	2L14	3.07	.18	.51	.57	14.00		.03	14	2	16	5.21		.14		
408.4	409.2	33885	.8	.8	2E36	3.74	.36	1.87	1.53	45.41		.17	8	21	30	2.92		.21		
409.2	410.5	33886	1.3	1.3	2B06	2.87	1.04	.57	.99	39.19		.66	2	4	7	4.16		.09		
410.5	412.7	33887	2.2	2.2	2E46	4.11	.26	3.70	2.81	81.18		.10	8	24	32	1.16		.31		
412.7	414.7	33888	2.0	1.6	1H4	2.85	.12	1.42	.40	41.06		1.65	8	4	13	3.07		.10		
414.7	421.0	33889	6.3	6.3	1H4	2.99	.24	1.43	.35	50.08		1.17	7	5	13	3.75		.14		
421.0	422.8	33890	1.8	1.8	2E46	4.02	.27	1.77	2.32	45.72		.22	8	24	33	2.40		.22		
422.8	425.8	33891	3.0	2.3	2D63	3.69	.15	.77	2.12	32.04		.62	4	16	21	11.08		.13		
425.8	429.3	33892	3.5	3.5	2G4	4.46	.07	5.25	9.03	93.00		.25	2	3	6	26.53		.09		
429.3	433.8	33893	4.5	4.5	2G4	4.47	.29	4.45	4.79	73.72		.25	5	3	9	7.41		.12		
433.8	438.8	33894	5.0	5.0	2E0&	4.56	.11	.96	.92	17.11		.10	1	35	37	.26		.06		
438.8	443.8	33895	5.0	5.0	2E0&	4.62	.23	2.14	1.53	37.32		.06	1	36	38	.16		.06		
443.8	447.0	33896	3.2	3.2	2E0&	4.55	.18	2.18	1.48	34.53		.07		35	36	.31		.01		
447.0	452.0	33897	5.0	5.0	2E1	3.96	.04	.42	.23	9.95		.08		29	29	.61		.01		
452.0	456.2	33898	4.2	4.2	2E1	4.30	.09	1.86	2.95	27.99		.09	2	24	27	3.54		.04		
456.2	461.2	33899	5.0	5.0	2D0&	3.30	.25	4.54	3.44	51.63		.08	6	7	14	.72		.05		
461.2	467.4	33900	6.2	6.1	2D0&	3.03	.27	1.37	3.31	24.57		.15	6	5	11	.50		.05		
467.4	469.1	33901	1.7	1.7	1H4	2.91	.58	.94	1.90	92.07		3.33	4	4	8	.47		.06		
469.1	474.0	33902	4.9	4.9	2D09	3.03	.27	1.15	3.44	68.12		.54	5	5	11	.58		.05		
474.0	478.0	33903	4.0	4.0	2E48	4.56	.20	1.72	3.02	20.84		.12	4	29	33	.17		.11		
478.0	481.3	33904	3.3	3.3	2E48	4.66	.29	1.73	2.83	10.89		.05	7	26	34	.14		.22		
481.3	485.5	33905	4.2	4.2	2E4	4.60	.13	1.99	5.69	9.95		.07	3	28	31	.36		.06		
485.5	489.8	33906	4.3	4.3	2G49	4.46	.24	3.99	9.08	21.15		.05	4	19	23	9.26		.16		
489.8	494.6	33907	4.8	4.8	2E49	4.43	.25	3.01	6.21	18.97		.03	5	24	30	.41		.17		
494.6	501.1	33908	6.5	6.5	2E49	4.53	.22	5.65	6.57	36.08		.03	5	22	27	1.12		.14		
501.1	505.0	33909	3.9	3.9	2G48	4.57	.18	6.33	10.39	59.10		.05	5	16	21	10.71		.22		
505.0	509.8	33910	4.8	4.8	2E4	4.58	.26	3.76	5.17	35.46		.04	5	23	28	5.68		.19		
509.8	514.8	33911	5.0	5.0	2E49	4.46	.30	2.11	3.93	22.40		.04	7	24	32	.29		.23		
514.8	519.8	33912	5.0	5.0	2E49	4.38	.31	1.89	3.20	17.11		.03	8	23	32	.17		.24		

DDH: 84F-19 UTM-N: 8896.6 UTM-E: 14700.0 UTM-ELEV: 3913.8 TOTAL DEPTH: 597.0 SECTION: 121+000
RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

-----DEPTHS----						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
519.8	524.8	33913	5.0	5.0	2E8&	4.45	.19	1.18	2.80	12.75		.03	10	23	33	.15		.25			
524.8	529.0	33914	4.2	4.2	2E48	4.69	.19	4.13	5.93	49.46		.03	6	24	30	.16		.25			
529.0	534.0	33915	5.0	4.0	2E4	4.50	.10	5.13	6.21	66.87		.04	4	22	27	.18		.17			
534.0	539.0	33916	5.0	4.9	2E4	4.51	.17	2.10	4.27	27.06		.03	4	27	31	.23		.06			
539.0	544.0	33917	5.0	4.9	2E4	4.51	.40	2.20	3.97	24.57		.04	7	25	32	.17		.07			
544.0	548.0	33918	4.0	3.8	2E4	4.88	.06	4.08	6.16	20.53		.03	1	28	30	.15		.03			
548.0	552.4	33919	4.4	4.4	2E4	4.73	.07	3.00	5.74	16.80		.06	1	28	30	.16		.02			
552.4	553.1	33920	.7	.7	1H4	3.29	.12	1.42	1.94	11.20		.03	4	13	17	.44		.06			
553.1	558.7	33921	5.6	5.6	2E4	4.71	.19	2.74	5.39	20.53		.04	3	28	31	.16		.03			
558.7	561.7	33922	3.0	3.0	2D0	3.19	.13	1.95	4.44	21.46		.03	5	7	12	.28		.07			
561.7	565.8	33923	4.1	4.1	2D0	2.91	.08	1.64	4.40	25.19		.06	4	2	6	.30		.05			
565.8	566.7	33924	.9	.9	2C0	2.88	.10	.30	.40	7.15		.02	3	2	6	.36		.04			
566.7	572.0	33925	5.3	5.3	0Q0&	2.72	.11	.83	.35	38.26		.02	1		1	.21		.02			
572.0	578.9	33926	6.9	6.5	0Q0&	2.84	.32	1.31	.48	141.52		.02	5		5	.17		.06			

DDH: 84F-20 UTM-N: 9099.0 UTM-E: 14901.6 UTM-ELEV: 3912.5 TOTAL DEPTH: 556.0 SECTION: 121+000
RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

-----DEPTHS-----		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %
348.8	350.3	33944	1.5	1.5	2C9	2.88	.64	.30	.48	27.06		.05	4	4	8	.42		.11		
350.3	351.9	33945	1.6	1.6	2E49	3.90	.22	3.79	4.67	73.41		.04		23	24	.22		.12		
351.9	355.0	33946	3.1	2.9	2E0	4.22	.05	1.02	1.27	17.42		.07	1	29	31	.45		.01		
355.0	356.7	33947	1.7	1.7	2G02	4.55	.10	2.53	3.72	32.97		.18	2	31	33	9.96		.03		
356.7	359.1	33948	2.4	2.4	2G4	4.61	.13	6.44	8.19	90.82		.06	1	19	20	10.43		.12		
359.1	362.1	33949	3.0	3.0	2G4	4.73	.12	6.75	8.84	94.25		.09	4	18	22	15.14		.07		
362.1	367.0	33950	4.9	4.5	2E4&	4.71	.17	7.22	7.97	139.03		.03	4	19	23	.50		.29		
367.0	368.2	33951	1.2	1.2	2E49	3.51	.33	4.28	.57	87.09		.05		22	22	.37		.01		
368.2	371.4	33952	3.2	3.0	2E46	4.59	.04	4.04	7.98	55.05		.03	1	33	34	2.95		.01		
371.4	375.4	33953	4.0	3.9	2D43	3.32	.09	4.14	8.40	58.48		.17		19	20	.22		.01		
375.4	379.5	33954	4.1	4.1	2D3	3.71	.07	1.29	3.08	16.80		1.37	2	26	28	.20		.12		
379.5	384.5	33955	5.0	5.0	2E4	4.78	.07	2.58	5.38	28.63		.04	1	15	17	.17		.05		
384.5	385.3	33956	.8	.8	2G1	4.62	.03	.60	.95	10.57		.07		28	29	6.32		.01		
385.3	389.3	33957	4.0	3.9	2E41	3.46	.04	1.72	3.19	28.30		.12		26	27	.18		.01		
389.3	393.0	33958	3.7	3.2	2E1	4.17	.04	.40	.64	12.75		.19	1	28	29	.17		.01		
393.0	397.0	33959	4.0	3.7	2E4	4.61	.07	5.32	7.22	85.23		.32	1	24	26	.15		.02		
397.0	399.1	33960	2.1	2.1	2E1	3.96	.16	3.78	3.72	22.71		.04	1	36	37	.21		.02		
399.1	402.3	33961	3.2	3.0	2E09	4.60	.27	1.11	.98	5.60		.04	1	37	38	.14		.03		
402.3	405.5	33962	3.2	2.0	2E09	4.71	.34	.60	3.46	3.01		.02	1	31	33	.14		.03		
405.5	407.3	33963	1.8	1.8	2C39	4.16	.29	.12	1.75	7.47		.08	1	23	24	.17		.02		
407.3	409.1	33964	1.8	1.8	2C35	3.82	.10	.59	3.29	7.78		.10	1	27	28	.18		.02		
409.1	414.0	33965	4.9	4.9	2C3&	4.03	.11	.53	1.59	6.22		.07	1	27	29	.15		.02		
414.0	418.9	33966	4.9	4.9	2C3&	4.18	.25	.06	1.22	11.51		.08	1	29	31	.15		.02		
418.9	423.8	33967	4.9	4.9	2C3&	4.13	.08	.17	.84	4.67		.08	1	18	19	.15		.02		
423.8	424.7	33968	.9	.9	2D39	3.50	.22	.36	4.85	8.71		.11	2	16	19	.27		.05		
424.7	425.7	33969	1.0	1.0	2C3	3.71	.13	.11	2.30	4.98		.10	1	23	25	.20		.02		
425.7	426.9	33970	1.2	1.2	2C53	3.58	.04	.16	1.24	3.42		.12		23	24	.20		.02		
426.9	428.7	33971	1.8	1.2	2D43	3.77	.20	8.34	6.25	55.37		.13	2	15	17	.22		.03		
428.7	432.8	33972	4.1	4.1	2C39	4.22	.26	.58	1.46	12.13		.10	1	31	33	.14		.02		
432.8	436.9	33973	4.1	4.0	2C39	3.86	.43	.83	.46	11.51		.09	1	25	27	.15		.05		
436.9	440.9	33974	4.0	4.0	2E48	4.42	.28	2.52	4.40	9.33		.04	7	27	34	.14		.05		
440.9	444.9	33975	4.0	4.0	2E89	4.54	.35	1.07	2.21	6.22		.03	7	32	39	.15		.23		
444.9	449.0	33976	4.1	4.1	2E89	4.48	.29	.48	2.34	4.98		.02	9	31	40	.15		.29		
449.0	452.2	33977	3.2	3.2	2E19	4.19	.42	.08	1.42	4.04		.05	5	29	35	.15		.15		
452.2	455.4	33978	3.2	3.2	2C39	3.92	.80	.17	1.27	10.26		.09	1	26	27	.14		.03		
455.4	458.6	33979	3.2	3.2	2C39	3.92	.29	.67	.59	8.40		.08	1	26	28	.15		.03		
458.6	461.0	33980	2.4	2.4	2D43	3.69	.16	3.86	9.57	14.00		.09	3	17	20	.20		.04		
461.0	465.7	33981	4.7	4.7	2C3	3.80	.14	.85	2.45	5.91		.08	4	13	17	.17		.09		
465.7	470.5	33982	4.8	4.8	2C39	3.89	.44	.28	.92	7.78		.08	3	27	30	.15		.08		
470.5	472.2	33983	1.7	1.7	2E41	3.99	.35	1.22	4.91	8.71		.08	5	25	30	.16		.14		
472.2	475.9	33984	3.7	3.7	2D39	4.20	.25	1.86	5.49	9.02		.06	4	27	32	.15		.14		
475.9	480.4	33985	4.5	4.5	2C39	3.91	.32	.65	2.65	6.22		.10	4	24	28	.13		.14		
480.4	484.8	33986	4.4	4.4	2D39	4.08	.48	1.61	2.68	8.71		.06	6	26	33	.14		.23		
484.8	487.0	33987	2.2	2.1	2E41	4.33	.11	4.54	9.63	14.62		.06	4	25	29	.15		.10		
487.0	492.0	33988	5.0	5.0	2D43	3.83	.07	3.42	8.55	20.53		.12	4	17	21	.18		.05		

DDH: 84F-21 UTM-N: 9503.5 UTM-E: 15296.3 UTM-ELEV: 3908.4 TOTAL DEPTH: 397.0 SECTION: 121+000
RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

-----DEPTHS----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
126.0	133.2	33927	7.2	7.0	2C37	3.15	.26	.10	.26	16.17		.03	9	7	16	.20		.05			
133.2	136.6	33928	3.4	3.4	2C37	3.34	.21	.09	.32	11.51		.03	17	7	24	.18		.04			
303.5	305.0	33929	1.5	1.5	2L12	2.90	.03	.22	.32	4.98		.04	2	2	4	.38		.06			
305.0	305.8	33930	.8	.8	2D03	3.17	.10	1.49	4.02	12.44		.08	6	3	9	.26		.04			
305.8	307.8	33931	2.0	2.0	2L14	2.81	.03	.11	.40	1.55		.10	2	2	4	.42		.05			
307.8	309.0	33932	1.2	1.2	2B7	2.82	.04	.27	.97	4.35		.06	2	2	4	.33		.06			
309.0	311.0	33933	2.0	2.0	2L14	2.94	.11	2.52	2.94	54.43		.30	5	4	9	.29		.05			
311.0	313.6	33934	2.6	2.0	2D37	3.14	.21	3.92	2.89	93.93		.53	5	3	8	.28		.05			

DDH: 84F-22 UTM-N: 9701.1 UTM-E: 15096.5 UTM-ELEV: 3752.0 TOTAL DEPTH: 185.0 SECTION: 119+000
RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

-----DEPTHS-----						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
47.0	48.3	33935	1.3	1.3	2C39	3.22	.22	.61	.27	46.03		1.71	8	11	19	.18		.02			
55.7	58.1	33936	2.4	2.3	2D0&	3.02	.13	1.80	4.35	33.28		.14	4	5	10	.24		.05			
70.7	75.3	33937	4.6	4.6	2D4&	3.24	.12	4.65	9.60	44.47		.23	5	5	10	.17		.03			
75.3	79.9	33938	4.6	4.6	2D4&	3.52	.09	4.10	11.48	25.51		.17	4	4	8	.17		.02			
79.9	84.6	33939	4.7	4.7	2B0&	2.70	.03	.09	.25	1.87		.02	3	1	4	.30		.13			
89.6	94.6	33940	5.0	5.0	2D0&	3.35	.13	1.71	6.95	17.73		.09	6	8	15	.18		.04			
94.6	99.6	33941	5.0	5.0	2D0&	3.12	.07	1.62	5.42	20.22		.13	3	7	11	.34		.02			
99.6	104.6	33942	5.0	5.0	2D4&	3.46	.09	2.60	8.02	31.73		.14	5	10	16	.26		.03			
104.6	109.5	33943	4.9	4.9	2D9&	3.09	.20	2.23	5.59	32.04			4	6	10	.32		.03			

DDH: 84F-24 UTM-N: 8082.8 UTM-E: 14307.2 UTM-ELEV: 3910.1 TOTAL DEPTH: 545.0 SECTION: 123+000
RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														S.G. W.R.
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	
435.5	439.0	34946	3.5	3.5	2A0	2.85	.05	.66	.48	14.00		.12		8	8	.33					.01
439.0	442.5	34947	3.5	3.3	2A0	2.94	.12	1.13	.36	21.77		.20		10	11	.36					.01
442.5	443.6	34948	1.1	1.1	2C5	3.22	.17	.18	.20	13.37		.19	1	12	14	.35					.02
443.6	446.3	34949	2.7	2.7	2A0	2.84	.08	.92	.88	11.51		.04	2	3	5	.61					.04
446.3	449.1	34950	2.8	2.5	2A4	2.79	.04	1.69	3.14	18.98		.08	2		3	.43					.05
449.1	451.8	34951	2.7	2.7	2E41	3.89	.20	4.76	8.87	74.34		.07	11	14	26	.21					.11
451.8	455.1	34952	3.3	3.3	2D0	3.02	.08	.76	4.03	15.86		.10	4	3	8	.44					.04
455.1	458.4	34953	3.3	3.3	2D0	2.94	.05	.54	4.12	11.82		.02	3	2	5	.50					.03
458.4	459.3	34954	.9	.9	2A0	2.96	.07	.49	2.06	9.95		.03	3	2	5	.38					.02
459.3	460.3	34955	1.0	1.0	2D5	3.06	.11	1.31	3.56	14.93		.03	3	3	7	.34					.02
460.3	463.0	34956	2.7	2.7	2A0	2.86	.07	.50	2.81	13.37		.16	4	2	6	.43					.04
463.0	466.9	34957	3.9	3.9	2D0	3.06	.16	.73	4.35	25.51		.19	5	5	10	.43					.04
466.9	468.1	34958	1.2	1.2	2D5	2.92	.07	.57	3.06	14.00		.21	5	2	7	.42					.04
468.1	470.3	34959	2.2	2.2	2A0	2.82	.06	.20	1.07	10.89		.03	3	2	5	.47					.02
470.3	471.6	34960	1.3	1.3	2B0&	3.00	.05	.11	.49	6.22		.04	3	2	5	.49					.03
471.6	472.6	34961	1.0	1.0	2A0	2.91	.05	.34	1.49	10.58		.13	2	1	3	.41					.02
472.6	473.9	34962	1.3	1.3	2B0	2.89	.06	.09	.55	7.46		.02	3	2	5	.42					.03
473.9	477.6	34963	3.7	3.7	2A0	2.90	.07	.18	.53	6.22		.02	3	2	6	.43					.02
477.6	481.3	34964	3.7	3.7	2B0&	2.86	.04	.71	2.23	11.82		.03	2	1	3	.36					.02
481.3	485.0	34965	3.7	3.7	2B4&	3.03	.07	1.19	2.91	20.22		.02	3	2	6	.35					.02
485.0	488.1	34966	3.1	3.1	2D0	3.03	.08	1.44	5.20	34.52		.05	6	2	8	.34					.03
488.1	491.2	34967	3.1	3.1	2D0	3.01	.10	1.47	3.96	46.03		.15	4	3	8	.37					.03
491.2	491.8	34968	.6	.6	2C5	3.03	.07	.79	3.14	23.95		.10	4	6	10	.27					.02
491.8	495.2	34969	3.4	3.3	2A0	2.78	.08	.26	1.43	14.00		.05	3	2	5	.35					.04
495.2	498.5	34970	3.3	3.3	2A0	2.84	.07	.61	1.20	11.82		.06	3	5	8	.37					.03

DDH: 84F-25 UTM-N: 8690.0 UTM-E: 14912.0 UTM-ELEV: 3911.0 TOTAL DEPTH: 591.0 SECTION: 123+015
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	ASSAYS														
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
281.5	282.6	35023	1.1	1.1	1E19	2.87	.12	.06	.17	2.80		.04	5	1	6	.30		.05			
282.6	283.9	35024	1.3	1.3	2C09	3.12	.24	.05	.10	5.29		.02	8	6	14	.18		.05			
283.9	287.9	35025	4.0	3.2	2C37	3.45	.41	.04	.12	5.29		.03	14	17	32	.15		.08			
287.9	291.9	35026	4.0	4.0	2C37	3.48	.48	.01	.36	2.18		.04	22	4	26	.16		.08			
291.9	296.9	35027	5.0	5.0	2C3*	3.57	.19	.04	.43	3.42		.09	5	8	14	.17		.08			
296.9	303.3	35028	6.4	6.4	2C3*	3.34	.31	.09	.40	4.04		.03	9	14	23	.16		.10			
303.3	304.6	35029	1.3	1.3	2A0	2.87	.11	.06	.09	.93		.02	5	3	8	.52		.10			
349.2	350.8	35030	1.6	1.6	2D09	3.39	.24	2.14	2.62	43.55		.28	6	12	18	.35		.08			
350.8	355.2	35031	4.4	4.4	2G4	4.73	.05	5.04	7.15	105.75		.34	2	18	21	18.91		.10			
355.2	356.4	35032	1.2	1.2	1H4	3.10	.37	1.88	2.98	54.74		.32	5	12	17	5.16		.22			
356.4	358.2	35033	1.8	1.8	2E4	4.54	.06	2.56	4.58	57.23		.14	4	31	36	.84		.12			
358.2	360.7	35034	2.5	2.5	2L4	2.91	.07	.27	.45	4.67		.02	2	4	7	4.41		.10			
360.7	364.8	35035	4.1	4.1	2E4&	4.36	.05	3.86	5.76	84.91		.12	6	24	31	2.05		.13			
364.8	366.9	35036	2.1	2.1	10E44	3.02	.05	.42	.40	6.53		.02	3	2	6	9.38		.10			
366.9	371.2	35037	4.3	4.3	2E1&	4.52	.05	2.90	2.92	54.43		.16	3	31	35	2.23		.22			
371.2	375.5	35038	4.3	4.3	2G4	4.36	.13	5.23	9.50	87.09		.19	7	4	12	26.40		.10			
375.5	381.4	35039	5.9	5.9	2E&8	4.50	.20	1.31	1.37	37.64		.10	8	31	40	.49		.21			
386.0	387.6	35040	1.6	1.6	2E13	3.57	.28	1.05	1.55	32.97		.33	2	22	25	3.04		.21			
393.8	399.7	35041	5.9	5.9	2E0&	4.66	.17	1.07	.69	21.78		.17	3	36	39	.26		.06			
399.7	405.8	35042	6.1	6.1	2E41	4.67	.06	2.19	1.88	24.58		.10	1	30	32	.22		.03			
405.8	410.0	35043	4.2	3.7	2C3	3.71	.06	.78	.33	32.97		2.19		19	19	.16		.02			
410.0	415.0	35044	5.0	5.0	2C3	3.44	.03	.40	.14	12.44		.60		18	19	.17		.01			
415.0	419.5	35045	4.5	4.5	2E1	4.53	.06	1.04	1.42	15.24		.15	1	35	36	.14		1.00			
419.5	420.9	35046	1.4	1.4	2E89	4.65	.41	1.88	1.67	24.26		.18	6	34	40	.17		.25			
420.9	423.0	35047	2.1	2.1	2E19	4.69	.23	1.86	2.90	20.84		.06		34	34	.14		.05			
423.0	428.0	35048	5.0	5.0	2F49	4.55	.33	4.82	6.84	50.08		.10	2	29	31	.89		.04			
428.0	433.3	35049	5.3	3.7	2F49	4.90	.33	5.04	7.30	71.85		.10	4	26	30	3.95		.20			
433.3	435.2	35050	1.9	1.9	2G4	4.52	.12	2.74	7.57	45.72		.05	2	17	19	23.33		.08			
435.2	437.5	35051	2.3	2.3	2E4	4.83	.07	2.18	5.17	23.33		.07	1	34	35	.65		.03			
437.5	441.2	35052	3.7	3.7	2E41	4.18	.24	2.09	2.52	37.64		.08	4	25	29	.28		.20			
441.2	443.8	35053	2.6	2.3	2E4	4.75	.14	4.63	8.25	56.61		.10	2	30	32	.17		.10			
443.8	448.8	35054	5.0	5.0	2E09	4.66	.27	3.30	2.53	38.57		.06	3	30	34	.15		.13			
448.8	453.8	35055	5.0	5.0	2E49	4.78	.35	2.25	3.04	35.15		.11	3	31	34	.15		.07			
453.8	458.7	35056	4.9	4.9	2E49	4.68	.21	3.32	2.13	8.88		.05	2	31	33	.16		.04			
458.7	464.5	35057	5.8	5.8	2E1	4.31	.14	1.31	.60	21.15		.05	1	31	33	.15		.21			
464.5	468.5	35058	4.0	4.0	2E41	4.43	.26	2.81	6.06	32.97		.06	5	26	31	.15		.06			
468.5	473.0	35059	4.5	4.3	2E41	4.52	.17	2.18	2.54	23.02		.06	2	31	33	.17		.38			
473.0	478.0	35060	5.0	5.0	2E48	4.49	.33	2.05	3.42	19.59		.05	9	25	34	.15		.28			
478.0	483.0	35061	5.0	5.0	2E48	4.47	.26	2.44	3.83	19.28		.04	7	27	34	.13		.15			
483.0	488.0	35062	5.0	5.0	2E48	4.18	.42	2.03	2.18	16.17		.06	5	25	31	.15		.18			
488.0	491.4	35063	3.4	3.4	2E48	4.53	.29	2.51	4.02	10.57		.03	6	25	32	.16		.03			
491.4	494.4	35064	3.0	3.0	2E4	4.99	.08	3.53	7.42	18.35		.04	2	32	34	.14		.04			
494.4	498.2	35065	3.8	3.8	2E4	4.88	.09	2.26	4.60	14.00		.05	2	32	34	.15		.04			
498.2	500.1	35066	1.9	1.9	2E4	4.86	.08	4.04	7.90	22.39		.04	2	32	35	.31		.05			
500.1	501.7	35067	1.6	1.6	2G41	3.57	.32	6.54	12.23	53.50		.07	7	8	16	.28		.04			
501.7	503.5	35068	1.8	1.8	2C09	3.06	.21	1.72	2.07	25.19		.03	6	5	12	.27		.04			
503.5	504.5	35069	1.0	1.0	1D4	2.91	.09	.32	1.31	3.73		.02	3	1	5	.52		.05			
504.5	505.8	35070	1.3	1.3	2C9	3.09	.20	1.16	1.62	15.86		.05	5		6	.38		.06			

DDH: 84F-25 UTM-N: 8690.0 UTM-E: 14912.0 UTM-ELEV: 3911.0 TOTAL DEPTH: 591.0 SECTION: 123+015
RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

						-----ASSAYS-----															
-----DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu	Pb	Zn	Ag(AA)	Ag(FA)	Au(FA)	Po	Py	TOT	BaO	Hg	Mn	As	Ba	S.G.
FROM	TO						%	%	%	g/mT	g/mT	g/mT	%	%	Fe	%	%	%	%	%	%
505.8	506.6	35071	.8	.8	1H4	3.36	.32	.10	1.95	4.98		.04	8	11	20	.62		.07			
506.6	512.0	35072	5.4	5.3	2059	3.14	.25	.25	.60	5.59		.04	5	6	12	.33		.03			
512.0	518.5	35073	6.5	6.5	2A0	2.80	.06	.35	.93	9.02		.03	2	1	3	.35		.03			
537.0	542.9	35074	5.9	5.9	0Q0&	3.01	.07	3.04	.46	57.85		.06	1		1	.14		.03			

DDH: 84F-26 UTM-N: 8986.0 UTM-E: 15204.3 UTM-ELEV: 3912.2 TOTAL DEPTH: 504.0 SECTION: 123+015
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	---ASSAYS---														
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
224.7	225.2	34971	.5	.5	2E47	3.48	.11	.70	12.27	51.01		.04	15		15	2.14		.08			
270.3	271.2	34972	.9	.9	2D39	3.81	.70	1.83	4.27	45.41		.23	8	14	23	.44		.08			
271.2	273.4	34973	2.2	.8	2G4	4.66	.05	3.77	7.69	51.01		.06	1	16	18	21.87		.02			
273.4	273.9	90002	.5	.0	FUDGE	2.75															
273.9	275.1	34974	1.2	1.2	2D4	3.93	.19	4.97	7.47	83.04		.82	2	13	16	.63		.08			
292.2	293.5	34975	1.3	.7	2C39	3.65	.21	.51	1.50	11.82		.33	5	16	21	.23		.06			
293.5	294.9	34976	1.4	1.4	2D4	4.29	.15	5.85	15.96	44.48		.35	8	6	15	.31		.29			
294.9	299.2	34977	4.3	4.3	2D4	3.51	.07	2.75	9.64	21.46		.34	4	7	11	.48		.10			
299.2	299.6	90003	.4	.0	FUDGE	2.75															
299.6	300.6	34978	1.0	1.0	2D09	3.35	.56	3.57	4.78	127.22		10.55	3	10	14	.27		.10			
300.6	301.7	34979	1.1	1.1	2D39	3.56	.40	2.33	2.15	129.70		2.67	7	13	20	.23		.09			
301.7	303.2	34980	1.5	1.5	2C39	3.35	.30	1.51	1.36	45.41		.28	10	9	19	.17		.13			
303.2	305.7	34981	2.5	2.5	2D4&	3.40	.12	5.75	15.40	45.41		.39	2	9	12	.22		.05			
305.7	306.2	34982	.5	.5	2D0&	3.12	.10	2.08	5.13	19.60		.07	3	9	12	.33		.10			
332.8	333.9	34983	1.1	1.1	2C39	3.69	.91	.40	3.07	27.06		.08	12	5	17	.15		.08			
333.9	335.4	34984	1.5	1.5	2E17	3.92	.33	.43	1.47	9.64		.02	32	1	33	.15		.08			
335.4	340.4	34985	5.0	5.0	2C39	4.14	.24	.47	1.44	9.64		.06	6	19	25	.15		.08			
340.4	345.4	34986	5.0	5.0	2C39	3.84	.36	.16	.89	5.29		.08	12	17	29	.15		.08			
345.4	350.4	34987	5.0	5.0	2C3&	3.71	.12	1.72	2.18	15.87		.11	7	16	24	.20		.04			
350.4	355.4	34988	5.0	5.0	2C39	3.53	.34	1.51	2.87	20.22		.21	6	12	18	.24		.05			
355.4	358.4	34989	3.0	3.0	2C39	3.24	.64	1.31	.32	33.90		.30	11	7	19	.20		.03			
358.4	360.5	34990	2.1	2.1	2C39	3.27	.19	.14	.31	6.84		.04	10	9	20	.21		.08			
365.0	368.0	34991	3.0	3.0	2D09	3.26	.46	1.60	3.10	27.06		.93	5	10	16	.26		.08			
368.0	370.5	34992	2.5	2.5	2D3	3.51	.11	1.31	3.92	13.37		.26	2	16	18	.22		.03			
370.5	375.2	34993	4.7	4.7	2C0&	3.26	.06	.37	1.34	7.46		.20	2	14	16	.26		.02			
375.2	378.2	34994	3.0	3.0	2C3	3.48	.09	.70	2.62	12.13		.19	2	15	17	.18		.02			
378.2	381.6	34995	3.4	3.4	2C39	3.51	.22	2.25	1.09	16.49		.16	2	15	17	.21		.02			
381.6	384.7	34996	3.1	3.1	2C3&	3.65	.11	.19	.41	7.46		.22	1	18	20	.22		.01			
384.7	388.1	34997	3.4	3.4	2C39	3.70	.34	.07	.47	1.56		.10	1	26	28	.16		.01			
388.1	391.5	34998	3.4	3.4	2C39	3.89	.22	.06	.88	6.53		.10	1	22	24	.18		.02			
391.5	394.9	34999	3.4	3.4	2C3	3.76	.25	.08	.37	6.00		.11	2	22	24	.18		.02			
394.9	396.1	35000	1.2	1.2	2A39	3.49	.21	.11	.61	1.87		.12	2	16	19	.22		.03			
396.1	399.5	35001	3.4	3.4	2C3	4.03	.07	.05	2.15	4.04		.08	2	24	26	.16		.02			
399.5	402.9	35002	3.4	3.4	2C3	3.87	.09	.06	1.22	2.49		.08	1	24	26	.17		.03			
402.9	406.3	35003	3.4	3.4	2C3&	3.84	.18	.48	2.79	3.11		.08	2	21	23	.18		.08			
406.3	409.8	35004	3.5	3.5	2C39	4.00	.34	.44	1.83	4.04		.05	4	22	27	.15		.24			
409.8	413.3	35005	3.5	3.5	2E89	4.04	.88	.12	1.32	6.84		.05	9	8	17	.13		.24			
413.3	416.8	35006	3.5	3.5	2E89	4.23	.27	.32	1.40	5.29		.10	8	25	34	.14		.16			
416.8	418.4	35007	1.6	1.6	2C39	3.65	.37	.05	.57	1.24		.05	7	14	21	.15		.24			
418.4	420.7	35008	2.3	2.3	2E89	4.55	.45	.04	1.58	3.73		.06	9	26	35	.14		.14			
420.7	423.7	35009	3.0	3.0	2C39	3.78	.48	.47	.94	4.98		.10	6	19	25	.14		.06			
423.7	426.4	35010	2.7	2.7	2C39	3.73	.46	.52	.99	5.60		.07	3	17	21	.14		.17			
426.4	428.3	35011	1.9	1.9	2C38	4.37	.33	1.37	.87	8.40		.10	6	22	29	.14		.12			
428.3	432.0	35012	3.7	3.7	2C3	3.71	.08	.66	1.62	6.53		.11	6	17	24	.14		.03			
432.0	433.8	35013	1.8	1.8	2D43	3.83	.06	5.67	7.48	12.75		.10	3	16	20	.16		.02			
433.8	437.7	35014	3.9	3.9	2C3	3.66	.06	.24	1.20	1.87		.12	2	19	21	.16		.02			
437.7	438.5	35015	.8	.8	2D3	3.64	.06	.37	6.01	2.80		.12	4	16	20	.20		.03			

DDH: 84F-26 UTM-N: 8986.0 UTM-E: 15204.3 UTM-ELEV: 3912.2 TOTAL DEPTH: 504.0 SECTION: 123+015
RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

-----DEPTHS-----						-----ASSAYS-----																
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.	
438.5	441.9	35016	3.4	3.4	2D3	3.74	.05	1.53	4.15	8.71		.12	2	18	20	.17		.02				
441.9	443.7	35017	1.8	1.7	2E4	4.63	.03	5.15	9.75	36.39		.10	2	29	31	.17		.02				
443.7	444.4	35018	.7	.7	2D4	3.52	.06	1.12	10.57	14.93		.14	5	12	17	.22		.04				
444.4	445.2	35019	.8	.8	2E0	4.73	.07	.41	1.86	5.91		.06	2	36	38	.13		.02				
445.2	445.7	35020	.5	.5	2E4	4.78	.04	1.76	8.19	16.49		.07	6	28	35	.13		.06				
445.7	446.4	35021	.7	.7	2D35	3.35	.11	1.75	3.22	26.12		.16	4	14	19	.26		.03				
446.4	449.0	35022	2.6	2.6	2D0	3.21	.15	2.18	7.13	27.68		.15	5	4	9	.30		.05				

DDH: 84F-27 UTM-N: 9188.5 UTM-E: 15400.9 UTM-ELEV: 3914.4 TOTAL DEPTH: 355.0 SECTION: 123+015
RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

-----DEPTHS---							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
238.7	240.7	35075	2.0	2.0	2C7	3.22	.09	.42	.41	11.20		.05	15		16	.58		.02			
240.7	243.3	35076	2.6	2.6	2C35	3.25	.11	.05	2.22	4.35		.12	22	1	23	.28		.02			
288.1	288.8	35077	.7	.7	2D7	3.01	.07	.74	5.85	6.53		.12	7		8	.24		.04			
316.5	318.0	35078	1.5	1.4	2C57	3.03	.11	.26	.74	6.22		.04	9	3	13	.43		.03			
318.0	318.7	35079	.7	.5	2H41	3.76	.11	1.57	20.21	23.02		.03	22	2	25	.15		.05			
322.6	325.3	35080	2.7	2.7	2C79	3.44	.24	.16	.36	5.91		.14	34	2	36	.17		.02			
325.3	326.5	35081	1.2	1.1	2C57	3.20	.29	.09	.81	3.42		.03	18		19	.21		.03			

[illegible]

DDH: 86F-05 UTM-N: 9616.3 UTM-E: 14880.0 UTM-ELEV: 3737.9 TOTAL DEPTH: 272.0 SECTION: 118+070
RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 315 DHD CALC: 1 SS CALC: 1

---DEPTHS---							---ASSAYS---															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.	
3.5	10.0	34731	6.5	6.5	2C35	3.44	.12	.65	1.46	11.00												
10.0	15.5	34732	5.5	5.5	2D34	3.44	.14	2.47	6.47	13.00												
15.5	19.5	34733	4.0	4.0	1D4	2.80	.06	.11	.08	6.00												
19.5	23.2	34734	3.7	3.7	2C3	3.40	.10	.60	.86	7.00												
24.2	28.0	34735	3.8	3.8	2C3	3.88	.10	1.16	1.22	13.00												
28.0	32.5	34736	4.5	4.5	1D4BX	3.22	.11	1.07	1.10	16.00												
32.5	39.2	34737	6.7	6.7	2D3	3.64	.14	1.89	3.41	17.00												
39.2	46.2	34738	7.0	7.0	2D3	3.68	.19	2.69	3.85	25.00												
46.2	50.0	34739	3.8	3.8	2C3	4.14	.30	.73	.45	10.00												
50.0	54.5	34740	4.5	4.5	2C3	4.26	.41	.70	.46	5.00												
54.5	58.5	34741	4.0	4.0	2D34	3.77	.42	4.23	6.21	37.00												
58.5	70.4	34742	11.9	11.9	1D4	2.88	.03	.10	.10	4.00												
70.4	75.5	34743	5.1	5.1	2C3	3.22	.21	1.24	1.27	20.00												
75.5	81.0	34744	5.5	5.5	2A34	3.78	.04	1.53	4.40	16.00												
81.0	87.0	34745	6.0	6.0	2A4	3.40	.06	4.40	9.94	25.00												
87.0	94.0	34746	7.0	7.0	2A4	3.43	.05	5.46	13.20	38.00												
94.0	101.0	34747	7.0	7.0	2A4	3.51	.07	6.46	7.12	107.00												
101.0	108.0	34748	7.0	7.0	2A4	3.38	.05	3.82	6.57	29.00												
108.0	114.0	34749	6.0	6.0	2A4	3.60	.04	2.56	6.64	23.00												
114.0	120.0	34750	6.0	6.0	2A4	3.24	.06	2.43	6.09	18.00												
120.0	125.0	35151	5.0	5.0	2C0	3.25	.06	.69	1.46	6.00												
125.0	131.0	35152	6.0	6.0	2D0	3.65	.08	1.87	6.61	15.00												
131.0	137.0	35153	6.0	6.0	2C0	3.17	.05	1.10	1.42	12.00												
137.0	143.0	35154	6.0	5.5	2C0	3.16	.07	.73	1.32	9.00												
143.0	149.0	35155	6.0	6.0	2D0	3.26	.08	1.07	3.80	12.00												
149.0	155.3	35156	6.3	5.8	2C0	3.22	.07	.78	1.59	13.00												
155.3	160.0	35157	4.7	4.7	2E4	4.87	.02	2.20	7.01	15.00												
160.0	163.5	35158	3.5	3.5	2E4	4.84		2.78	6.31	16.00												
163.5	167.0	35159	3.5	3.0	2A4	3.48	.03	3.41	8.00	26.00												
167.0	172.5	35160	5.5	5.2	2A4	3.71	.04	5.48	10.00	42.00												
172.5	177.0	35161	4.5	4.1	2A4	3.76	.05	2.34	8.41	28.00												
177.0	179.5	35162	2.5	2.0	2E4	4.58	.03	5.06	9.56	33.00												
179.5	185.0	35163	5.5	5.0	2D34	3.34	.23	4.77	6.67	79.00												
185.0	190.0	35164	5.0	4.2	1D149	2.92	.08	2.38	4.50	35.00				3	2	5						
190.0	193.0	35165	3.0	3.0	2D479	3.23	.16	3.91	9.68	35.00				9	3	12						
193.0	196.0	35166	3.0	3.0	2D479	3.38	.12	1.97	17.60	26.00				11		11						
196.0	202.0	35167	6.0	6.0	2D479	3.24	.23	4.24	6.76	43.00				13	1	14						
202.0	207.0	35168	5.0	4.8	2D4	3.40	.08	3.99	11.20	42.00				3	2	6						
207.0	212.0	35169	5.0	5.0	2D4	2.96	.09	2.68	8.20	35.00												
212.0	217.0	35170	5.0	4.6	2D4	3.01	.07	3.41	8.42	44.00												
217.0	222.0	35171	5.0	4.9	2D4	2.94	.06	2.48	7.36	33.00												
222.0	227.0	35172	5.0	5.0	2D4	2.93	.07	2.59	5.69	29.00												
227.0	232.0	35173	5.0	5.0	2D4	3.18	.09	4.90	10.90	55.00												
232.0	237.0	35174	5.0	5.0	2D4	3.56	.05	5.54	11.80	36.00												
237.0	241.0	35175	4.0	3.6	2D4	3.59	.05	5.30	10.20	27.00												
241.0	244.0	35176	3.0	2.8	2D4	3.11	.10	3.68	8.62	34.00												
244.0	249.0	35177	5.0	4.7	1D49	2.83	.06	.81	.44	54.00												

DDH: 86F-06 UTM-N: 9407.0 UTM-E: 14667.5 UTM-ELEV: 3713.7 TOTAL DEPTH: 364.0 SECTION: 118+070
RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 315 DHD CALC: 1 SS CALC: 1

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	---ASSAYS---													
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %
7.0	12.2	34511	5.2	5.2	1D4	2.86	.08	.09	.04	12.00										
12.2	18.0	34512	5.8	5.8	2H34	3.92	.24	3.56	5.39	80.00										
18.0	24.0	34513	6.0	6.0	2C0	3.07	.08	.24	.40	8.00										
24.0	29.5	34514	5.5	5.5	1H49	2.85	.08	.89	.78	18.00										
29.5	34.5	34515	5.0	5.0	1H49	3.22	.26	2.45	1.60	45.00										
34.5	39.5	34516	5.0	5.0	1H49	3.53	.19	3.84	2.59	84.00										
39.5	42.0	34517	2.5	2.5	2E0	4.51	.21	1.54	.36	65.00										
42.0	47.0	34518	5.0	5.0	2F4	4.60	.26	7.13	6.69	121.00										
47.0	52.1	34519	5.1	5.1	2F4	5.01	.15	4.53	4.91	83.00										
52.1	56.0	34520	3.9	3.9	2F4	4.40	.19	5.29	4.69	93.00										
56.0	61.0	34521	5.0	5.0	2F4	4.60	.12	6.19	6.21	92.00										
61.0	65.8	34522	4.8	4.8	2E14	4.33	.05	1.59	2.92	21.00										
65.8	69.8	34523	4.0	4.0	2E1	4.14	.04	.48	.60	11.00										
69.8	74.0	34524	4.2	4.2	2E1	4.16	.04	.29	.12	7.00										
74.0	77.8	34525	3.8	3.8	2E0	4.67	.05	.74	.51	12.00										
77.8	81.3	34526	3.5	3.5	2E0	4.78	.47	1.00	.23	16.00										
81.3	85.0	34527	3.7	3.7	2E0	4.58	.35	1.12	.30	18.00										
85.0	90.6	34528	5.6	5.6	2E1	4.58	.09	.49	.08	10.00										
90.6	95.6	34529	5.0	5.0	2E14	4.77	.04	2.33	3.71	22.00										
95.6	100.6	34530	5.0	5.0	2E8	4.51	.29	1.12	2.28	17.00										
100.6	104.7	34531	4.1	4.1	2E8	4.37	.20	1.31	1.85	17.00										
104.7	108.1	34532	3.4	3.1	2E14	4.46	.13	1.88	2.67	20.00										
108.1	112.1	34533	4.0	4.0	2E14	4.72	.17	2.04	3.41	23.00										
112.1	115.8	34534	3.7	3.7	2E1	4.70	.08	.91	.93	14.00										
115.8	119.7	34535	3.9	3.9	2E14	4.84	.14	2.46	2.22	21.00										
119.7	123.5	34536	3.8	3.8	2E14	4.07	.14	2.82	7.42	16.00										
123.5	127.6	34537	4.1	4.1	2E84	4.27	.28	3.29	5.60	11.00										
127.6	132.0	34538	4.4	4.4	2E84	4.71	.13	3.64	8.48	14.00										
132.0	137.0	34539	5.0	5.0	2E84	4.79	.15	2.42	6.21	15.00										
137.0	142.0	34540	5.0	5.0	2E84	4.71	.10	3.61	6.23	18.00										
142.0	147.0	34541	5.0	5.0	2E84	4.71	.21	3.17	6.61	16.00										
147.0	153.0	34542	6.0	6.0	2E84	4.42	.23	2.54	5.25	9.00										
153.0	157.5	34543	4.5	4.5	2F41	3.96	.14	4.18	11.60	11.00										
157.5	162.0	34544	4.5	4.4	2E81	4.51	.43	.72	2.31	4.00										
162.0	164.5	34545	2.5	2.5	2E81	4.43	.50	.39	1.81	4.00										
164.5	171.0	34546	6.5	4.6	2E4	4.97	.02	4.23	7.45	16.00										
171.0	176.0	34547	5.0	5.0	2E4	4.76	.03	4.20	8.37	18.00										
176.0	179.2	34548	3.2	3.2	2E4	4.83	.02	3.24	6.75	15.00										
179.2	183.5	34549	4.3	4.3	2E4	4.98	.03	5.39	8.03	20.00										
183.5	186.7	34550	3.2	3.2	2D4	3.64	.06	3.59	7.00	16.00										
186.7	190.4	34701	3.7	3.7	2D0	3.28	.17	1.10	3.82	14.00										
190.4	193.5	34702	3.1	3.1	2D0	3.26	.21	1.08	3.31	13.00										
193.5	197.0	34703	3.5	3.5	2A0	2.97	.07	.65	2.69	18.00										
197.0	201.0	34704	4.0	4.0	2A4	3.20	.03	1.73	2.70	19.00										
201.0	206.3	34705	5.3	5.3	2A4	3.21	.04	1.45	6.43	18.00										
206.3	212.5	34706	6.2	6.2	2A0	3.00	.03	1.11	2.03	14.00										
212.5	216.5	34707	4.0	4.0	2A34	3.77	.03	2.34	2.42	19.00										
216.5	222.9	34708	6.4	6.4	2E415	4.41	.02	4.69	12.70	24.00										
222.9	228.5	34709	5.6	5.6	2E415	4.43	.03	3.72	5.19	36.00										
228.5	233.2	34710	4.7	4.7	2D5	3.52	.04	.93	3.21	13.00										
233.2	238.0	34711	4.8	4.8	2D5	3.91	.03	1.60	2.75	15.00										

DDH: 86F-06 UTM-N: 9407.0 UTM-E: 14667.5 UTM-ELEV: 3713.7 TOTAL DEPTH: 364.0 SECTION: 112+070
RFE: 92 RFE DIR: 235 PLUNGE ANGLES: 0 315 DHD CALC: 1 SS CALC: 1

[illegible]

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	ASSAYS														S.G. U.R.
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	
364.5	367.3	34801	2.8	.6	2C3	2.79	.12	.18	.12	5.00											
367.3	369.5	34802	2.2	2.2	1H49	3.31	.29	1.69	.25	32.00											
369.5	373.3	34803	3.8	2.9	2C0	3.70	.30	.27	.11	13.00											
373.3	377.5	34804	4.2	3.5	2E4	3.46	.11	2.93	5.77	29.00											
377.5	380.0	34805	2.5	2.5	2E4	3.31	.16	1.51	4.73	23.00											
380.0	383.7	34806	3.7	2.7	2D4	4.04	.24	3.87	7.39	52.00											
383.7	387.5	34807	3.8	3.5	2D4	2.99	.09	4.07	6.17	37.00											
387.5	392.0	34808	4.5	4.5	2E4	4.43	.12	5.00	6.59	52.00											
392.0	395.5	34809	3.5	3.0	2E4	4.93	.08	4.02	6.75	39.00											
395.5	399.0	34810	3.5	3.0	2E4	4.67	.06	7.56	10.30	72.00											
399.0	403.0	34811	4.0	2.0	2E4	4.77	.34	3.61	5.85	46.00											
403.0	407.5	34812	4.5	3.0	2E4	4.94	.40	6.05	7.64	64.00											
407.5	411.5	34813	4.0	4.0	2E4	5.12	.29	6.82	8.84	61.00											
411.5	416.2	34814	4.7	4.7	2E4	4.62	.31	7.51	8.88	71.00											
416.2	420.5	34815	4.3	4.3	2E4	4.83	.12	6.80	8.56	60.00											
420.5	425.3	34816	4.8	4.5	2E4	4.76	.08	6.92	8.85	54.00											
425.3	429.0	34817	3.7	3.5	2E4	4.68	.27	5.87	7.89	59.00											
429.0	433.7	34818	4.7	4.7	2G4	4.76	.11	6.95	8.03	71.00											
433.7	437.8	34819	4.1	4.1	2G4	4.44	.12	7.46	8.18	74.00											
437.8	442.0	34820	4.2	4.0	2G0	5.35	.11	3.58	2.69	46.00											
442.0	446.0	34821	4.0	3.8	2G4	5.42	.28	5.95	6.99	66.00											
446.0	450.5	34822	4.5	4.5	2E4	3.51	.25	3.96	5.78	47.00											
450.5	454.0	34823	3.5	3.0	2E4	4.65	.16	5.65	8.34	40.00											
454.0	462.0	34824	8.0	8.0	2H4	4.91	.48	9.34	13.10	114.00											
462.0	467.0	34825	5.0	5.0	2B4	3.54	.24	8.68	11.80	138.00											
467.0	477.0	34826	10.0	10.0	2L12	2.93	.09	.09	.38	4.00											
477.0	488.5	34827	11.5	11.5	1D194	2.85	.05	.34	.51	23.00											
488.5	493.9	34828	5.4	5.3	2A0	2.96	.21	.32	.47												

PAGE : 237

[illegible]

DDH: 86F-10 UTM-N: 8546.0 UTM-E: 13949.8 UTM-ELEV: 3873.9 TOTAL DEPTH: 522.0 SECTION: 119+000
RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 315 DHD CALC: 1 SS CALC: 1

[illegible]

DDH: 86F-11 UTM-N: 9114.9 UTM-E: 14711.4 UTM-ELEV: 3739.5 TOTAL DEPTH: 337.0 SECTION: 120+000
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 315 DHD CALC: 1 SS CALC: 1

-----DEPTHS-----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
165.2	169.0	35201	3.8	3.8	2G74	4.20		5.47	7.87	95.00		.10	12	14	27						
169.0	173.5	35202	4.5	4.5	1H4	2.90		1.31	.87	24.00		.07	6	5	12						
173.5	180.9	35203	7.4	3.7	1H4	3.70		4.19	3.47	69.00		.07	16	13	29						
180.9	184.8	35204	3.9	3.9	2E4*	4.20		8.66	8.15	140.00		.24	12	19	31						
184.8	193.0	35205	8.2	6.7	1H4	3.20		2.72	2.75	14.00		1.17	5	8	13						
193.0	198.0	35206	5.0	3.9	2E46	4.50		2.07	2.47	17.00		.55	2	35	37						
198.0	202.0	35207	4.0	4.0	2E0	4.80		1.59	1.54	16.00		.03	3	37	41						
202.0	207.0	35208	5.0	4.3	2E0	4.30		.35	.15	14.00		.03	1	36	37						
207.0	211.0	35209	4.0	3.0	2E0	4.50		.72	.19	9.00			1	39	41						
211.0	217.0	35210	6.0	3.9	2E0	4.50		.31	.16	5.00			1	40	41						
217.0	223.0	35211	6.0	3.7	2E4	5.00		2.74	3.15	12.00		.21	1	39	41						
223.0	228.5	35212	5.5	5.5	2E18	4.80		.90	.73	24.00		.69	5	36	41						
228.5	233.5	35213	5.0	5.0	2E80	4.50		1.45	.40	20.00		.14	6	35	41						
233.5	238.3	35214	4.8	4.8	2E48	4.80		2.75	2.47	36.00		.17	5	36	42						
238.3	243.5	35215	5.2	5.2	2E80	4.50		.45	.33	9.00		.03	7	34	42						
243.5	246.6	35216	3.1	3.1	2GE4	4.50		4.39	4.48	73.00			7	24	31						
246.6	251.0	35217	4.4	4.4	2E0	4.30		1.14	1.14	11.00			12	28	40						
251.0	255.9	35218	4.9	4.2	2E0	4.30		.66	.56	11.00			10	31	42						
255.9	260.4	35219	4.5	4.5	2E0	4.55		.82	.56	15.00			8	33	42						
260.4	265.0	35220	4.6	4.6	2E0	4.50		1.79	1.78	20.00			6	33	40						
265.0	271.0	35221	6.0	6.0	2E0	4.80		1.33	2.19	16.00			4	36	41						
271.0	277.5	35222	6.5	5.9	2E4	4.50		2.84	3.15	26.00			2	39	42						
277.5	283.0	35223	5.5	5.5	2E814	4.50		2.15	3.27	22.00			5	32	38						
283.0	286.5	35224	3.5	3.5	2E814	4.30		3.15	4.86	18.00			5	28	33						
286.5	291.0	35225	4.5	4.5	2E814	4.30		2.27	3.05	60.00			5	32	37						
291.0	296.0	35226	5.0	5.0	2E814	4.50		2.37	4.71	7.00			5	31	37						
296.0	303.0	35227	7.0	7.0	2A43	3.80		2.75	7.83	36.00			4	17	21						
303.0	307.8	35228	4.8	4.8	2ED	4.00		1.01	.92	27.00			9	25	34						
307.8	312.2	35229	4.4	4.4	2D5	4.00		3.74	7.60	18.00			19	10	30						

DDH: 86F-12 UTM-N: 8993.8 UTM-E: 14596.9 UTM-ELEV: 3740.5 TOTAL DEPTH: 463.0 SECTION: 120+000
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 315 DHD CALC: 1 SS CALC: 1

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	---ASSAYS---														S.G. W.R.
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	
185.6	190.3	35230	4.7	4.7	2E341	3.70		2.17	5.20	24.00			10	17	28						
190.3	194.5	35231	4.2	3.6	2C07	3.00		.40	.20	8.00		.07	4	4	9						
194.5	199.0	35232	4.5	4.5	2C07	3.00		.26	.42	6.00		.45	4	11	15						
199.0	204.0	35233	5.0	5.0	2C37	3.70		.24	.75	4.00		.38	2	25	28						
204.0	209.0	35234	5.0	5.0	2C37	3.70		.75	2.02	10.00		.34	2	23	26						
209.0	213.9	35235	4.9	4.7	2G4	4.50		6.40	6.98	70.00		.58	4	22	26						
213.9	217.5	35236	3.6	3.6	2G4	4.80		7.36	6.56	74.00		.24	6	22	29						
217.5	222.1	35237	4.6	4.6	2G4	4.80		6.42	6.87	74.00		.14	2	20	22						
222.1	227.1	35238	5.0	4.8	2G4	4.50		7.60	6.87	90.00		.27	4	24	29						
227.1	231.7	35239	4.6	4.6	2G4	4.80		5.66	6.65	80.00		.24	1	23	24						
231.7	235.8	35240	4.1	4.1	2G4	4.80		5.86	6.89	98.00		.21	3	19	22						
235.8	238.7	35241	2.9	2.9	2H43	4.30		4.45	6.73	70.00		.14	17	15	33						
238.7	243.2	35242	4.5	4.5	1D219	3.00		.73	.84	12.00		.14	2	4	7						
243.2	247.0	35243	3.8	3.8	1D219	3.00		.52	.66	4.00		.03	2	2	4						
247.0	252.0	35244	5.0	4.6	1D219	3.00		.75	1.09	14.00		.07	3	3	7						
252.0	256.0	35245	4.0	4.0	1D19*	3.00		1.94	1.83	44.00			3	5	8						
256.0	260.7	35246	4.7	4.7	BXA	3.70		.42	3.46	94.00			14	14	28						
260.7	264.5	35247	3.8	3.8	2H43	4.50		6.46	8.88	104.00			18	17	35						
264.5	268.5	35248	4.0	4.0	2H43	4.30		6.63	8.51	98.00			26	12	39						
268.5	271.5	35249	3.0	3.0	2A4	3.30		2.37	7.24	38.00			6	6	13						
271.5	275.5	35250	4.0	4.0	2H43	4.30		5.66	7.84	74.00			16	20	37						
275.5	279.8	35251	4.3	4.3	1D419	2.90		.77	.69	18.00		.24	3	3	7						
279.8	282.8	35252	3.0	3.0	2EH	4.20		5.19	3.42	70.00		.03	13	21	35						
282.8	288.8	35253	6.0	6.0	2E4	4.80		4.26	4.47	32.00		.07	2	36	39						
288.8	292.0	35254	3.2	3.1	2G4	4.50		6.11	7.22	42.00			2	18	21						
292.0	295.7	35255	3.7	3.7	2G4	4.50		6.29	7.56	50.00			2	20	23						
295.7	301.0	35256	5.3	2.3	2F4	4.80		1.57	3.16	8.00			3	40	44						
301.0	305.0	35257	4.0	4.0	2F4	4.50		5.92	10.10	40.00			1	34	35						
305.0	309.8	35258	4.8	4.8	2F4	4.80		3.95	6.52	20.00		.03	5	34	40						
309.8	314.0	35259	4.2	4.2	2E81	4.50		.97	1.95	10.00			5	37	43						
314.0	323.2	35260	9.2	.7	2E81	5.00		1.54	1.43	10.00			5	38	43						
323.2	327.0	35261	3.8	3.5	2E4	4.80		4.11	7.00	20.00			3	37	41						
327.0	332.0	35262	5.0	5.0	2E4	4.80		2.95	4.21	20.00			3	38	42						
332.0	335.9	35263	3.9	3.9	2E4	5.00		2.25	2.67	12.00			3	39	43						
335.9	342.0	35264	6.1	2.1	2E0	4.80		1.95	2.23	10.00			3	41	45						
342.0	347.8	35265	5.8	4.6	2E4	4.80		2.32	5.33	14.00			3	39	42						
347.8	352.8	35266	5.0	5.0	2E4	5.00		2.75	5.65	16.00		2.85	2	41	43						
352.8	357.7	35267	4.9	4.9	2E0	4.30		1.37	1.44	12.00			1	33	34						
357.7	362.4	35268	4.7	4.7	2E4	5.00		3.23	5.14	22.00			1	40	42						
362.4	366.8	35269	4.4	4.4	2E4	4.80		2.66	5.15	18.00			4	35	40						
366.8	370.2	35270	3.4	3.4	2AE4	3.40		1.73	4.01	18.00			5	11	17						
370.2	374.2	35271	4.0	4.0	2AE4	3.70		3.00	5.05	30.00		.07	5	16	21						
374.2	378.4	35272	4.2	4.2	2D5	3.10		2.04	3.28	26.00			5	7	13						
378.4	383.6	35273	5.2	5.0	2D5	3.00		3.33	4.22	44.00			5	5	11						
383.6	387.9	35274	4.3	4.3	2A43	4.50		6.67	7.25	60.00		.24	2	36	38						
387.9	393.0	35275	5.1	5.1	2A4	3.40		1.84	3.69	22.00		.03	2	1	3						
393.0	398.5	35276	5.5	5.2	2A4	2.80		2.11	2.75	22.00		.03	2	1	3						
398.5	403.5	35277	5.0	5.0	2A4	2.80		1.76	4.46	30.00		.48	1		2						
403.5	407.0	35278	3.5	.5	2A4	2.70		2.28	3.72	36.00		.14	2	2	4						
407.0	411.8	35279	4.8	4.8	2A4	3.10		1.06	1.34	16.00		.38	2	2	5						
411.8	416.2	35280	4.4	4.4	2A43	4.70		8.67	8.65	129.00		.72	4	28	33						

DDH: 86F-12 UTM-N: 8993.8 UTM-E: 14596.9 UTM-ELEV: 3740.5 TOTAL DEPTH: 463.0 SECTION: 120+000
RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 315 DHD CALC: 1 SS CALC: 1

-----DEPTHS----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
416.2	420.7	35281	4.5	4.5	2A4	2.90		1.20	2.62	22.00		.51	1	5	6						
420.7	425.3	35282	4.6	4.6	2A4	3.30		1.61	3.28	34.00		.72	1	7	8						
425.3	430.0	35283	4.7	4.7	2A4	3.20		4.50	4.06	106.00		.96	1	9	11						
430.0	434.5	35284	4.5	4.5	2A4	3.30		1.17	3.33	30.00		.69		13	14						
434.5	439.0	35285	4.5	4.5	2A4	3.00		1.52	3.29	34.00		.51	1	8	9						
439.0	443.0	35286	4.0	4.0	2A4	3.00		1.31	3.34	30.00		.14	2	7	9						
443.0	448.0	35287	5.0	5.0	2A43	4.40		1.44	4.86	22.00		.27	5	15	20						
448.0	452.8	35288	4.8	4.8	2A4	3.10		1.63	4.06	26.00		.07	3	5	9						
452.8	457.4	35289	4.6	4.6	2A4	2.90		1.31	4.84	20.00		1.47	3	2	5						

DDH: 86F-14 UTM-N: 9361.6 UTM-E: 14564.2 UTM-ELEV: 3706.9 TOTAL DEPTH: 270.0 SECTION: 118+000
RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 315 DHD CALC: 1 SS CALC: 1

-----DEPTHS----						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
102.7	108.0	35333	5.3	4.7	2GL	4.20		3.82	4.50	44.00		.10	8	19	27						
108.0	111.5	35334	3.5	3.4	2J814	4.00		2.71	2.01	14.00			41		41						
111.5	118.0	35335	6.5	6.5	2E4	4.40		3.30	3.00	44.00			5	33	39						
118.0	126.0	35336	8.0	6.5	2E4	4.30		3.87	4.04	52.00			17	19	37						
126.0	132.2	35337	6.2	6.2	2E0	4.60		1.82	1.36	26.00		.27	12	28	41						
132.2	135.2	35351	3.0	3.0	2J81	4.00		1.15	1.26	8.00			43	3	46						
135.2	139.8	35338	4.6	3.3	2E4	4.50		8.26	8.46	88.00		.27	2	28	30						
139.8	144.0	35339	4.2	3.8	2E0@	4.50		.56	.35				12	26	39						
144.0	150.2	35340	6.2	6.2	2E4	4.40		2.94	3.09	28.00			4	33	38						
150.2	156.5	35341	6.3	6.3	2E44	4.30		5.91	8.23	50.00			1	33	35						
156.5	161.0	35342	4.5	4.4	2E0	4.70		1.25	1.74	16.00			6	33	40						
161.0	165.2	35343	4.2	4.2	2E0	4.70		.95	1.68	12.00			4	34	39						
165.2	170.2	35344	5.0	5.0	2E0	4.70		1.24	2.25	10.00			4	34	39						
170.2	174.7	35345	4.5	3.7	2E4	4.50		1.42	2.94	8.00			4	31	35						
174.7	180.0	35346	5.3	5.0	2E4BX	4.50		2.71	4.05	10.00			6	27	33						
180.0	185.0	35347	5.0	5.0	2E4	4.60		2.67	4.74	26.00				38	39						
185.0	190.4	35348	5.4	5.4	2E4	4.60		3.75	6.34	14.00			1	38	39						
190.4	195.0	35349	4.6	4.6	2E4	4.50		2.66	3.59	12.00				40	41						
195.0	199.5	35350	4.5	4.5	2E4	4.70		4.22	9.28	18.00			1	33	35						
199.5	204.0	35352	4.5	4.5	2E4	4.70		2.28	5.99	8.00		.21	1	38	40						
204.0	209.5	35353	5.5	5.5	2E14	4.50		2.71	5.70	10.00			3	32	36						
209.5	215.0	35354	5.5	5.5	2E4	4.80		3.33	6.72	8.00			1	37	38						
215.0	220.0	35355	5.0	5.0	2A47	3.60		3.03	5.80	38.00			17	8	26						
220.0	225.0	35356	5.0	5.0	2D57	3.10		1.47	2.80	14.00		.03	8	4	13						
225.0	229.0	35357	4.0	3.9	2C79	3.30		.11	1.18			.03	5	11	17						
229.0	233.0	35358	4.0	4.0	2C579	3.30		.44	1.35	4.00			29	4	34						
233.0	237.5	35359	4.5	4.5	2D79	3.50		1.56	5.11	16.00		.07	9	13	22						
237.5	243.5	35360	6.0	6.0	2A44	3.90		4.95	9.79	36.00		.14	2	18	21						
243.5	248.0	35361	4.5	4.5	2A44	3.20		4.05	9.18	18.00		.14	4	8	12						

DDH: 86F-15 UTM-N: 8757.8 UTM-E: 14787.0 UTM-ELEV: 3737.5 TOTAL DEPTH: 416.5 SECTION: 121+000
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 315 DHD CALC: 1 SS CALC: 1

-----DEPTHS-----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
128.0	133.5	35362	5.5	5.5	2E4	4.40		2.01	2.85	38.00		.07	9	26	35						
133.5	135.5	35363	2.0	2.0	2G4	4.30		3.50	7.25	63.00			1	17	18						
135.5	141.3	35364	5.8	3.9	2E4	4.60		6.40	8.28	110.00		.07	11	20	31						
141.3	145.1	35365	3.8	3.8	2E4	4.20		5.72	8.32	95.00		.07	14	20	34						
145.1	148.3	35366	3.2	3.2	2D43	3.70		3.79	8.49	69.00		.07	13	11	24						
148.3	153.0	35367	4.7	4.7	2C0	3.00		.17	.18	8.00			4	5	10						
153.0	157.5	35368	4.5	4.4	1H49	3.10		.21	.22	6.00			5	3	8						
157.5	162.5	35369	5.0	4.9	2C03	3.50		1.71	.50	53.00			14	18	33						
162.5	166.5	35370	4.0	4.0	1H4*9	4.00		4.33	4.27	80.00		.03	10	14	24						
166.5	172.5	35371	6.0	6.0	1H49	2.80		.39	.22	8.00			9	5	14						
172.5	177.0	35372	4.5	4.3	1E19	2.80		.25	.29	6.00		.03	1	2	4						
177.0	182.4	35373	5.4	5.4	1E19	3.00		.59	.92	10.00		.27	2	4	6						
182.4	187.0	35374	4.6	4.6	1D49	3.20		1.02	.46	21.00		.27	3	5	8						
187.0	191.8	35375	4.8	4.7	1D49	3.10		1.22	1.58	25.00		.21	3	4	7						
191.8	195.3	35376	3.5	3.4	1H49	3.70		3.64	4.30	57.00			11	13	25						
195.3	198.8	35377	3.5	3.5	1H49	3.00		1.79	.47	34.00			3	2	6						
198.8	203.8	35378	5.0	5.0	1E19	2.90		.26	.48	6.00			1	2	4						
203.8	209.8	35379	6.0	5.5	1D9	3.10		.67	1.44	11.00			5	6	11						
209.8	214.3	35380	4.5	4.5	1D9	2.90		.65	1.11	11.00			2	2	5						
214.3	219.4	35381	5.1	5.1	1D9	3.10		.97	1.09	15.00			2	5	8						
219.4	224.7	35382	5.3	4.2	2E4	4.50		4.24	4.33	51.00			2	29	31						
224.7	228.2	35383	3.5	3.5	2E4	3.40		7.18	4.71	118.00			7	9	16						
228.2	233.5	35384	5.3	2.0	2E1	4.50		2.13	1.58	27.00				38	39						
233.5	238.5	35385	5.0	1.8	2E1	4.00		.48	.28	10.00				31	32						
238.5	246.0	35386	7.5	6.2	2E1	3.70		.60	.39	30.00				25	26						
246.0	251.5	35387	5.5	5.0	2E1	4.10		1.09	.51	76.00				34	35						
251.5	258.5	35388	7.0	3.1	2E1	4.20		.47	.15	11.00			1	34	35						
258.5	264.5	35389	6.0	4.6	2E1	4.40		1.24	.97	17.00			2	35	38						
264.5	269.5	35390	5.0	3.5	2E1	4.40		1.39	1.18	17.00				37	38						
269.5	276.2	35391	6.7	4.7	2E1	4.00		.61	.95	11.00			1	34	36						
276.2	280.5	35392	4.3	4.3	2E14	4.70		2.67	1.69	30.00			2	41	43						
280.5	284.5	35393	4.0	4.0	2E1	4.70		1.24	1.98	17.00			3	39	43						
284.5	289.0	35394	4.5	4.5	2F4	5.00		6.50	7.25	30.00			4	33	38						
289.0	294.3	35395	5.3	5.3	2F4	4.50		5.44	8.12	21.00			5	30	36						
294.3	298.0	35396	3.7	3.7	2F4	4.90		3.43	6.47	17.00			3	36	40						
298.0	302.2	35397	4.2	4.2	2F4	4.60		3.49	7.74	19.00			2	36	39						
302.2	307.1	35398	4.9	4.9	2F4	4.60		4.40	8.50	22.00			5	29	35						
307.1	310.9	35399	3.8	3.8	2F4	4.60		7.75	12.97	46.00			7	23	30						
310.9	314.5	35400	3.6	3.6	2F4	4.70		7.58	11.23	60.00			7	24	32						
314.5	318.5	35401	4.0	4.0	2F4	4.70		5.79	6.80	48.00			6	28	34						
318.5	322.8	35402	4.3	4.3	2E4	4.70		2.17	3.55	17.00			5	34	39						
322.8	327.0	35403	4.2	4.2	2E4	4.70		5.82	8.71	26.00			2	33	36						
327.0	331.2	35404	4.2	4.2	2E4	5.00		2.14	5.21	13.00			1	39	40						
331.2	335.1	35405	3.9	3.9	2E0	4.90		1.03	1.91	11.00				43	44						
335.1	339.6	35406	4.5	4.5	2E0	4.90		.19	1.97	6.00				46	47						
339.6	345.5	35407	5.9	5.0	2E4	4.90		3.55	6.42	20.00				41	42						
345.5	348.8	35408	3.3	3.3	2E4	4.90		5.31	10.02	32.00			1	37	39						
348.8	353.5	35409	4.7	4.7	2E4	4.90		3.49	9.26	23.00			2	36	38						
353.5	357.5	35410	4.0	4.0	2E4	4.50		1.90	3.90	22.00			6	32	38						
357.5	360.1	35411	2.6	2.6	2H34	4.60		6.16	9.25	40.00			12	26	38						
360.1	365.5	35412	5.4	5.4	2D3	3.60		2.37	5.34	20.00			7	12	19						

DDH: 86F-15 UTM-N: 8757.8 UTM-E: 14787.0 UTM-ELEV: 3737.5 TOTAL DEPTH: 416.5 SECTION: 121+000
RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 315 DHD CALC: 1 SS CALC: 1

-----DEPTHS----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
365.5	370.5	35413	5.0	5.0	2C05	3.00		1.23	2.24	18.00			4	3	7						
370.5	375.0	35414	4.5	4.4	2A4	3.00		1.56	4.29	21.00			2	2	5						
375.0	384.0	35415	9.0	8.9	1D419	2.90		.04	.06	2.00			4	1	5						
384.0	387.8	35416	3.8	3.8	2A0	3.10		.24	.66	10.00			3	9	13						
387.8	392.7	35417	4.9	4.7	2A0	3.10		.19	.75	11.00			6	7	13						
392.7	396.8	35418	4.1	4.1	2A0	3.10		.11	.42	7.00			5	6	12						
396.8	401.4	35419	4.6	4.6	1D09	2.80		.34	.25	21.00			2	3	5						
401.4	406.5	35420	5.1	5.1	2A0	3.00		.20	.39	6.00			2	3	6						
406.5	410.7	35421	4.2	4.2	2A0	3.00		.26	1.58	8.00			3	4	8						

DDH: 86F-16 UTM-N: 9426.4 UTM-E: 14738.8 UTM-ELEV: 3706.7 TOTAL DEPTH: 297.0 SECTION: 118+00
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 315 DHD CALC: 1 SS CALC: 1

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	---ASSAYS---													
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %
11.0	18.5	34551	7.5	7.5	2G4	4.50		6.58	7.70	91.00		.21	3	13	17					
18.5	25.5	34552	7.0	6.7	2E14	4.60		1.69	2.45	19.00		.10		35	36					
25.5	29.5	34553	4.0	4.0	2G4	4.70		4.37	8.05	44.00		.03		26	26					
29.5	33.5	34554	4.0	4.0	2G4	4.70		4.34	7.42	44.00		.07		26	27					
33.5	37.0	34555	3.5	3.5	2E4	4.60		2.10	3.86	26.00		.17	2	37	39					
37.0	40.5	34556	3.5	3.4	2E4	4.90		3.35	4.20	27.00		.07		36	36					
40.5	45.5	34557	5.0	5.0	2C3	3.60		.11	.17	2.00		.03		28	28					
45.5	50.6	34558	5.1	5.1	2C3@	4.10		.52	.60	6.00		.10		33	34					
50.6	57.0	34559	6.4	6.4	2E1	4.30		.76	1.10	10.00		.10	1	32	33					
57.0	62.6	34560	5.6	4.2	2E1	4.90		1.40	1.54	12.00		.07		45	46					
62.6	67.8	34561	5.2	5.2	2E1	4.50		.82	.41	18.00		.17		38	39					
67.8	69.5	34562	1.7	1.7	2E14	4.00		3.94	4.49	49.00		.34	1	22	24					
69.5	75.0	34563	5.5	5.5	2E484	4.50		5.57	7.72	25.00		.10	5	28	34					
75.0	80.0	34564	5.0	5.0	2E484	4.80		9.22	13.60	45.00		.10	6	24	31					
80.0	84.6	34565	4.6	4.6	2E484	5.00		6.12	9.07	40.00		.21	7	33	40					
84.6	88.3	34566	3.7	3.7	2E8	4.80		.66	1.82	8.00		.17	6	35	42					
88.3	93.0	34567	4.7	4.7	2E1	3.90		.63	1.23	16.00		.65	1	29	31					
93.0	98.2	34568	5.2	5.2	2D443	4.60		9.81	13.63	28.00		.21	3	20	24					
98.2	101.7	34569	3.5	3.5	2C3	4.30		.16	.68	4.00		.27	1	32	33					
101.7	105.0	34570	3.3	3.3	2D3	3.90		2.93	1.99	36.00		1.51		27	28					
105.0	109.0	34571	4.0	4.0	2D3	3.70		1.41	5.33	12.00		.24	1	25	27					
109.0	113.5	34572	4.5	4.5	2D3	3.80		.53	3.76	8.00		.17	2	24	26					
113.5	116.5	34573	3.0	3.0	2C3	3.70		.38	.82	12.00		.31		28	28					
116.5	120.0	34574	3.5	3.5	2E81	4.10		.87	2.49	6.00		.10	5	28	34					
120.0	124.5	34575	4.5	4.5	2E481	4.00		8.89	16.00	17.00		.10	6	19	25					
124.5	129.5	34576	5.0	5.0	2E481	3.90		4.69	4.97	7.00		.14	4	20	25					
129.5	134.8	34577	5.3	5.3	2E481	4.00		6.01	6.53	10.00		.14	5	17	22					
134.8	139.0	34578	4.2	4.2	2E81	3.90		.16	2.28	2.00		.10	5	23	29					
139.0	144.0	34579	5.0	5.0	2E81	3.90		.14	1.10	4.00		.10	5	24	29					
144.0	149.4	34580	5.4	5.4	2E81	4.30		.10	1.80	6.00		.07	8	32	40					
149.4	152.0	34581	2.6	2.5	2C3	3.60		.29	1.91	12.00		.03	4	19	23					
152.0	154.8	34582	2.8	2.8	2E81	4.40		.24	1.56	4.00			5	36	41					
154.8	159.0	34583	4.2	4.2	2E481	4.20		2.60	6.09	6.00			5	27	33					
159.0	164.0	34584	5.0	5.0	2E481	4.40		1.22	3.40	6.00			6	29	36					
164.0	168.0	34585	4.0	4.0	2E814	4.40		1.91	2.46	8.00		.07	3	32	35					
168.0	172.6	34586	4.6	4.6	2E81	4.40		.12	1.12	4.00		.07	5	36	42					
172.6	177.0	34587	4.4	4.4	2E41	4.50		3.92	8.68	10.00		.03	2	30	32					
177.0	182.0	34588	5.0	4.5	2E41	4.70		6.71	11.96	19.00		.03	1	34	36					
182.0	187.0	34589	5.0	4.7	2EA4	4.10		1.54	5.94	8.00		.07	1	31	32					
187.0	191.0	34590	4.0	4.0	2EA4	4.10		1.84	6.84	10.00		.10		29	30					
191.0	198.0	34591	7.0	4.7	2A34	3.80		4.56	7.76	21.00			1	37	38					
198.0	202.6	34592	4.6	4.6	2A34	4.10		1.63	7.19	11.00		.07		25	26					
202.6	208.6	34593	6.0	6.0	2A34	3.80		2.75	6.05	16.00		.07		20	21					
208.6	215.0	34594	6.4	6.4	2E4	4.70		5.36	9.42	6.00		.03	1	36	37					
215.0	222.5	34595	7.5	7.5	2D345	3.80		3.56	7.56	10.00		.17	3	19	22					
222.5	228.2	34596	5.7	5.7	2C0	3.20		.61	1.12	24.00		.14	6	9	16					
228.2	234.0	34597	5.8	5.8	2D0	.50		.15	5.94	6.00		.03	3	13	17					
234.0	238.7	34598	4.7	4.7	2A34	4.00		5.15	12.32	38.00		.17	2	19	22					
238.7	244.8	34599	6.1	6.1	2E14	4.00		3.27	4.34	28.00		.14	5	26	31					
244.8	249.0	34600	4.2	4.2	2C0	3.30		.77	.61	15.00		.14	4	7	12					
249.0	253.8	35083	4.8	4.7	2C0	3.20		.26	.51	9.00		.14	3	12	16					

DDH: 86F-16 UTM-N: 9426.4 UTM-E: 14738.8 UTM-ELEV: 3706.7 TOTAL DEPTH: 297.0 SECTION: 118+00
RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 315 DHD CALC: 1 SS CALC: 1

-----DEPTHS-----				-----ASSAYS-----																
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
253.8	259.2	35084	5.4	5.4	205	2.90	.49	1.72	13.00		.34	5	6	11						
259.2	265.5	35085	6.3	6.3	1D194	2.80	.54	.18	17.00		.17	3	2	5						
265.5	271.5	35086	6.0	6.0	1D194	2.80	.22	.40	7.00		.03	1	2	3						

DDH: 86F-17 UTM-N: 9534.4 UTM-E: 14831.4 UTM-ELEV: 3708.7 TOTAL DEPTH: 325.0 SECTION: 118+070
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 315 DHD CALC: 1 SS CALC: 1

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
7.0	11.5	35470	4.5	4.5	2GAC	3.60		4.20	12.52	42.00				3	15	19					
11.5	17.0	35471	5.5	4.7	2A4	3.50		2.14	5.84	26.00				2	16	19					
17.0	21.8	35472	4.8	4.8	2A4	3.60		3.15	6.07	68.00					18	19					
21.8	26.0	35473	4.2	4.2	2C3	4.10		.35	1.25	12.00				1	36	37					
26.0	31.0	35474	5.0	5.0	2C3	4.10		.13	.72	6.00				2	36	39					
31.0	36.0	35475	5.0	5.0	2C3	4.00		.39	1.37	8.00				4	30	34					
36.0	42.0	35476	6.0	6.0	2C3	4.00		.31	.89	8.00				3	30	34					
42.0	48.0	35477	6.0	5.9	2C3	3.90		.19	1.12	6.00				2	29	31					
48.0	53.2	35478	5.2	5.0	2D3	4.20		1.96	4.38	16.00				1	30	32					
53.2	59.0	35479	5.8	5.8	2C09	3.30		1.08	1.30	36.00				3	12	16					
59.0	64.0	35480	5.0	5.0	2C09	3.50		.06	.48	8.00					25	26					
64.0	70.0	35481	6.0	5.3	2D0	3.70		.02	.18	6.00				2	26	28					
70.0	76.0	35482	6.0	6.0	2C0	3.50		1.50	4.24	16.00				2	18	20					
76.0	81.0	35483	5.0	5.0	2E10	4.00		.10	.99	2.00					30	31					
81.0	86.0	35484	5.0	5.0	2E10	3.90		.25	.99	8.00				2	28	30					
86.0	93.0	35485	7.0	7.0	2E10	4.00		.63	2.04	8.00					33	34					
93.0	99.0	35486	6.0	6.0	2E10	3.90		.71	1.88	10.00					29	30					
99.0	105.0	35487	6.0	6.0	2CE	3.50		2.09	3.72	26.00				1	21	22					
105.0	111.5	35488	6.5	6.5	2CE	4.00		.10	.78	16.00				1	29	30					
111.5	116.0	35489	4.5	4.5	2C3	4.00		.05	.73	14.00				1	30	31					
116.0	122.0	35490	6.0	6.0	2C3	4.00		.07	1.21	16.00					30	31					
122.0	127.5	35491	5.5	5.5	2C3	4.10		.06	2.49	8.00					32	33					
127.5	132.5	35492	5.0	5.0	2C3	4.10		.04	2.46	4.00				2	30	33					
132.5	137.5	35493	5.0	5.0	2C3	3.90		.87	2.48	12.00				1	27	29					
137.5	143.0	35494	5.5	5.5	2C3	3.90		.32	2.33	8.00				1	27	28					
143.0	146.8	35495	3.8	3.8	2C3	4.10		.03	.41	4.00				1	32	34					
146.8	152.0	35496	5.2	5.2	2C3	4.00		.05	1.43	4.00				1	29	31					
152.0	156.5	35497	4.5	4.5	2C3	3.90		.28	2.07	6.00					27	28					
156.5	160.0	35498	3.5	3.5	2E1	3.90		.08	2.65	4.00					25	26					
160.0	164.0	35499	4.0	4.0	2E14	4.00		2.25	4.22	10.00				1	23	24					
164.0	168.7	35500	4.7	4.7	2D354	3.90		5.68	6.68	26.00				3	15	18					
168.7	173.0	35141	4.3	4.3	2D354	3.80		3.39	9.43	20.00				1	23	24					
173.0	178.0	35142	5.0	5.0	2D35	3.50		2.95	6.77	28.00				3	17	20					
178.0	183.0	35143	5.0	5.0	2AD	3.20		1.54	2.76	22.00				3	10	14					
183.0	188.0	35144	5.0	5.0	2C05	3.10		1.12	2.60	16.00				2	4	6					
188.0	193.0	35145	5.0	5.0	2C05	2.90		.36	.98	10.00				3	8	11					
193.0	198.0	35146	5.0	5.0	2C05	3.00		.63	1.81	12.00				2	9	11					
198.0	203.0	35147	5.0	5.0	2C05	3.20		.29	.95	6.00				6	14	20					
203.0	211.5	35148	8.5	7.5	2C05	3.30		.69	2.68	14.00				4	15	19					
211.5	218.5	35149	7.0	5.3	2C05	3.30		.36	.35	18.00				4	16	20					
218.5	223.0	35150	4.5	3.4	2D05	3.50		3.23	5.10	40.00				4	15	20					
223.0	226.0	35087	3.0	3.0	2D05	3.10		3.24	2.37	44.00				6	10	16					
226.0	230.6	35088	4.6	4.6	2B4	2.90		2.04	6.72	30.00				2	1	4					
230.6	235.5	35089	4.9	4.9	2B4	2.80		1.86	3.47	24.00				2	2	5					
235.5	240.3	35090	4.8	4.8	2B4	3.00		4.46	4.12	50.00				3	3	6					
240.3	244.7	35091	4.4	4.4	2B4	2.90		3.64	5.15	36.00				2	2	5					
244.7	249.0	35092	4.3	4.3	2B4	3.00		3.43	8.66	46.00				3	1	4					
249.0	252.5	35093	3.5	3.5	2A4	3.00		4.20	9.31	58.00				2	2	4					
252.5	255.5	35094	3.0	3.0	2B45	3.00		1.10	3.35	32.00				2	3	6					
255.5	266.0	35095	10.5	9.3	1D419	3.00		1.99	4.48	94.00				3	2	5					
266.0	270.7	35096	4.7	4.7	2B45	3.00		3.81	6.12	76.00				2	2	5					

DDH: 86F-17 UTM-N: 9534.4 UTM-E: 14831.4 UTM-ELEV: 3708.7 TOTAL DEPTH: 325.0 SECTION: 118+070
RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 315 DHD CALC: 1 SS CALC: 1

-----DEPTHS----						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
270.7	275.3	35097	4.6	4.6	2B45	3.00		3.29	5.15	32.00			3	3	7						
275.3	280.2	35098	4.9	4.9	2B45	3.00		4.67	6.78	60.00			2	1	4						
280.2	285.1	35099	4.9	4.9	2B45	3.10		4.28	10.51	52.00			2	1	3						
285.1	290.0	35100	4.9	4.9	2B45	3.00		4.87	4.99	50.00			3	2	6						
290.0	295.1	04964	5.1	5.1	2B45	3.20		2.95	6.76	42.00			3	1	5						
295.1	300.0	04965	4.9	4.9	2B45	3.00		2.09	7.27	38.00			2	1	3						
300.0	305.0	04966	5.0	5.0	2C0	3.00		.86	2.52	19.00			3	4	7						

DDH: 86F-18 UTM-N: 9363.8 UTM-E: 14961.4 UTM-ELEV: 3704.5 TOTAL DEPTH: 277.0 SECTION: 120+000
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 315 DHD CALC: 1 SS CALC: 1

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %
14.0	18.4	35104	4.4	4.4	2E18	3.90		.18	1.32	4.00		.21	4	27	32					
18.4	22.8	35105	4.4	4.4	1H4*	3.30		1.74	.48	25.00		.89	5	14	20					
22.8	29.0	35106	6.2	5.8	2E18	3.90		.19	.70	8.00		.24	5	28	34					
29.0	35.0	35107	6.0	6.0	2E18	4.00		.58	.71	6.00		.10	2	32	34					
35.0	39.8	35108	4.8	4.8	2A34	3.40		3.20	6.01	28.00		.27	4	14	19					
39.8	42.6	35109	2.8	2.8	2D7	3.30		3.14	6.05	32.00		.58	15	4	20					
42.6	46.0	35110	3.4	3.4	2C7	3.40		.50	.20	17.00		.51	16	6	23					
46.0	50.3	35111	4.3	4.3	1D4	3.10		1.28	.07	38.00		.99	3	4	8					
50.3	55.6	35112	5.3	4.4	10Q9	3.10		.29	.09	12.00		.65	2	14	16					
55.6	60.6	35113	5.0	5.0	2E18	3.60		.90	2.32	40.00		.38	5	18	24					
60.6	65.6	35114	5.0	5.0	2E18	3.90		.29	1.15	30.00		.10	1	29	30					
65.6	70.6	35115	5.0	5.0	2E18	3.90		.08	1.15	6.00		.07	2	30	32					
70.6	75.6	35116	5.0	5.0	2E18	3.80		.05	.69	6.00		.10	6	29	35					
75.6	80.6	35117	5.0	5.0	2E18	3.80		.56	.84	16.00		.07	2	29	31					
80.6	85.6	35118	5.0	5.0	2E18	4.10		.22	1.03	4.00		.07	1	32	34					
85.6	90.6	35119	5.0	5.0	2E18	3.70		.23	1.01	6.00		.21	1	27	28					
90.6	94.6	35120	4.0	4.0	2E18	3.80		.19	1.83	4.00		.14	1	29	30					
94.6	100.1	35121	5.5	5.5	2E18	4.20		.12	.72	6.00		.17	1	31	32					
100.1	104.0	35122	3.9	3.9	2E18	4.10		.06	.18	4.00		.14		34	34					
104.0	108.5	35123	4.5	4.5	2E18	4.00		.53	.28	14.00		.24		36	36					
108.5	113.8	35124	5.3	5.3	2E18	4.00		1.09	.46	20.00		.21		26	27					
113.8	118.0	35125	4.2	3.0	2E18	4.20		.17	.50	8.00		.21	1	37	38					
118.0	123.0	35126	5.0	5.0	2E18	4.50		.44	1.71	6.00		.07	5	30	35					
123.0	128.0	35127	5.0	5.0	2E18	3.80		.43	.86	4.00			6	26	32					
128.0	132.1	35128	4.1	4.1	2E18	3.90		.06	1.29	6.00			9	28	38					
132.1	135.0	35129	2.9	2.9	2E18	4.40		.09	.30	8.00		.10	7	34	41					
135.0	139.8	35130	4.8	4.8	2E1	4.00		.32	.91	10.00		.17	2	30	33					
139.8	144.0	35131	4.2	4.2	2E1	4.10		.39	1.68	8.00		.17	1	33	35					
144.0	148.5	35132	4.5	.0	2E1	4.50		.24	1.98	4.00		.10	3	35	39					
148.5	152.0	35133	3.5	.0	2E1	4.40		1.13	2.58	4.00		.07	3	34	37					
152.0	156.0	35134	4.0	4.0	2E14	4.20		1.80	4.14	6.00		.07	1	29	31					
156.0	160.0	35135	4.0	4.0	2E1	4.00		.40	1.80	4.00		.10	1	30	31					
160.0	165.2	35136	5.2	5.2	2E1	4.10		1.06	2.57	8.00		.17	1	28	30					
165.2	167.6	35137	2.4	2.4	2D0	3.90		2.09	6.67	20.00		.24	2	20	22					
167.6	171.0	35138	3.4	3.4	2D4	3.90		3.45	8.19	28.00		.24	3	20	23					
171.0	174.5	35139	3.5	3.5	2E4	4.90		7.01	19.30	58.00		.31	3	27	30					
174.5	178.2	35422	3.7	3.7	2E4	5.00		4.10	9.31	32.00			1	36	37					
178.2	183.6	35423	5.4	2.9	1D49	2.90		.80	.93	12.00			2	3	5					
183.6	190.0	35424	6.4	6.4	2D0	2.90		1.46	3.56	24.00			4	3	7					
190.0	195.3	35425	5.3	5.3	2D0	3.10		1.11	3.59	20.00			6	3	10					
195.3	199.7	35426	4.4	4.4	10Q9	3.00		3.63	5.74	80.00			6	1	8					
199.7	202.0	35427	2.3	2.3	2D0	2.90		1.00	4.26	26.00			1	1	3					
202.0	206.7	35140	4.7	4.7	2D0	3.00		2.19	3.63	52.00		.51	2	2	4					
206.7	211.1	35428	4.4	4.4	2A0	2.90		1.62	2.36	22.00			2	2	4					
211.1	215.4	35429	4.3	4.3	2A4	3.10		3.60	7.39	74.00			4	6	11					
215.4	220.1	35430	4.7	4.7	2A4	3.10		2.79	5.76	40.00			2	5	8					
220.1	225.1	35431	5.0	5.0	2A4	3.00		1.09	3.76	18.00			1	5	6					
225.1	229.1	35432	4.0	4.0	2D5	3.10		1.47	4.87	30.00			1	4	5					
229.1	234.0	35433	4.9	4.9	2D5	3.00		1.07	4.20	16.00			1	3	5					
234.0	238.2	35434	4.2	4.2	2D5	3.00		1.71	5.05	24.00			2	2	4					
238.2	243.2	35435	5.0	5.0	2D5	3.00		2.49	6.82	36.00			2	1	4					

DDH: 86F-18 UTM-N: 9363.8 UTM-E: 14961.4 UTM-ELEV: 3704.5 TOTAL DEPTH: 277.0 SECTION: 120+000
RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 315 DHD CALC: 1 SS CALC: 1

-----DEPTHS-----						-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
243.2	247.7	35436	4.5	4.5	2D5	3.10	4.66	3.90	155.00			1	3	5						
247.7	251.9	35437	4.2	4.2	2D5	3.20	3.40	3.98	74.00			3	4	8						
251.9	256.1	35438	4.2	4.2	2C0	3.20	.34	1.12	14.00			2	4	7						
256.1	260.3	35439	4.2	4.2	2C0	3.00	1.25	.21	24.00			3	3	7						
260.3	265.0	35440	4.7	4.7	2C0	2.90	1.57	.56	54.00			2	3	6						

DDH: 86F-19 UTM-N: 9300.0 UTM-E: 14898.0 UTM-ELEV: 3702.6 TOTAL DEPTH: 313.0 SECTION: 120+000
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 315 DHD CALC: 1 SS CALC: 1

-----DEPTHS-----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
100.9	105.0	35441	4.1	4.1	2D5	3.50		.62	4.35	10.00				2	17	20					
105.0	111.7	35442	6.7	6.7	2C35	3.80		.18	1.08	6.00				1	28	30					
111.7	117.0	35443	5.3	5.3	2E810	4.20		.12	.75	6.00				6	30	36					
117.0	122.6	35444	5.6	5.6	2E180	4.00		.05	.99	4.00				4	30	34					
122.6	127.0	35445	4.4	4.4	2C38	3.90		.04	1.76	4.00				7	22	29					
127.0	132.3	35446	5.3	5.3	2C38	3.90		.35	2.16	4.00				7	25	33					
132.3	137.0	35447	4.7	4.7	2C38	4.00		.70	1.71	6.00				6	25	31					
137.0	141.0	35448	4.0	4.0	2C38	3.90		1.00	1.99	14.00				8	26	34					
141.0	145.2	35449	4.2	4.2	2C38	3.60		2.77	1.21	56.00				4	19	24					
145.2	151.1	35450	5.9	5.9	2E81	4.10		.47	2.15	10.00				6	29	36					
151.1	154.4	35451	3.3	3.3	2E41	4.20		5.63	10.00	16.00				2	27	30					
154.4	158.3	35452	3.9	3.9	2E41	4.20		4.26	9.46	12.00				2	26	29					
158.3	164.0	35453	5.7	5.7	2D354	3.60		2.82	8.13	18.00				2	18	20					
164.0	170.5	35454	6.5	6.5	2D354	3.50		2.62	9.46	22.00				3	17	21					
170.5	175.7	35455	5.2	5.1	2E4	4.80		3.33	8.29	22.00				3	34	38					
175.7	178.6	35456	2.9	2.9	2A34	3.90		4.03	11.90	38.00				2	20	23					
178.6	183.5	35457	4.9	4.9	2A0	2.90		1.41	1.73	20.00				2	2	5					
183.5	188.9	35458	5.4	4.7	2A0	3.00		1.05	2.19	16.00				4	8	12					
188.9	192.0	35459	3.1	3.1	2A0	2.90		.55	2.26	12.00				1	18	20					
192.0	199.3	35460	7.3	7.3	2D5	3.10		.97	3.66	16.00				2	8	11					
199.3	204.0	35461	4.7	4.7	2C0	2.80		.16	.17	14.00				2	3	5					
204.0	209.0	35462	5.0	4.9	2C0	3.00		.07	.12	6.00				3	4	8					
209.0	214.0	35463	5.0	4.7	2C0	3.00		.25	.71	10.00				3	4	7					
214.0	224.0	35464	10.0	10.0	1D419	2.80		.60	.39	14.00				2	1	3					
224.0	233.5	35465	9.5	9.5	1D419	2.80		.22	.31	6.00				2	2	4					
233.5	243.0	35466	9.5	9.5	1D419	2.90		.24	.22	12.00				2	1	4					
243.0	251.0	35467	8.0	8.0	1D29	2.80		.10	.19	2.00				2	1	3					
251.0	259.0	35468	8.0	7.7	1D419	2.80		.38	.73	8.00				2	1	4					
259.0	267.0	35469	8.0	8.0	1D419	2.80		.36	.83	8.00				3	2	6					

DDH: 86F-20 UTM-N: 9350.7 UTM-E: 14843.4 UTM-ELEV: 3705.4 TOTAL DEPTH: 257.0 SECTION: 119+070
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 315 DHD CALC: 1 SS CALC: 1

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
11.0	21.8	10653	10.8	9.9	2E4@	4.10		4.14	6.46	48.00			2	27	30						
21.8	27.0	10654	5.2	4.1	2E1	4.60		1.28	1.43	16.00			1	38	40						
27.0	30.5	10655	3.5	2.3	2E1	4.40		.19	.31	8.00			1	35	37						
30.5	36.5	10656	6.0	5.4	2A3	3.60		.29	.83	6.00				24	24						
36.5	41.5	10657	5.0	4.3	2A34	3.50		1.07	4.92	16.00			1	19	20						
41.5	44.6	10658	3.1	2.7	2C3	4.00		.87	1.90	14.00			1	31	32						
44.6	49.0	10659	4.4	4.2	2C3	4.20		1.07	2.08	6.00			7	29	37						
49.0	54.5	10660	5.5	5.2	2E4	4.40		1.80	4.19	8.00			7	30	38						
54.5	59.5	10661	5.0	4.6	2E4	4.20		1.96	3.99	8.00			6	28	35						
59.5	64.0	10662	4.5	4.4	2E4	4.40		2.57	4.14	12.00			8	29	37						
64.0	68.5	10663	4.5	4.5	2E0	4.50		1.22	2.11	6.00			8	30	39						
68.5	72.7	10664	4.2	4.1	2E0	4.10		.07	1.64	4.00			6	31	37						
72.7	78.0	10665	5.3	5.1	2E0	4.20		.03	.67	2.00			2	34	37						
78.0	83.0	10666	5.0	4.9	2E0	4.20		.21	1.89	4.00			4	32	36						
83.0	87.5	10667	4.5	4.3	2E0	4.20		.24	.63	6.00			1	34	36						
87.5	93.0	10668	5.5	5.4	2A34	3.70		2.21	5.23	8.00			1	24	26						
93.0	97.2	10669	4.2	4.1	2A3	3.80		.36	2.15	4.00			2	28	30						
97.2	101.8	10670	4.6	4.3	2A34	3.30		2.96	5.78	36.00			2	11	14						
101.8	106.8	10671	5.0	4.8	2A34	3.70		1.23	3.22	14.00			1	33	35						
106.8	113.0	10672	6.2	5.1	2E1	4.00		.43	3.37	6.00			5	29	34						
113.0	117.0	10673	4.0	3.2	2E1	3.80		.14	1.72	4.00			5	28	33						
117.0	121.2	10674	4.2	2.5	2E81	3.80		.06	1.01	6.00			5	26	31						
121.2	126.5	10675	5.3	5.1	2E81	3.80		.09	1.63	2.00			4	28	32						
126.5	131.8	10676	5.3	5.2	2E81	4.00		.06	1.74	4.00			6	30	36						
131.8	136.8	10677	5.0	4.9	2C3	3.60		.10	.83	4.00			5	23	28						
136.8	141.0	10678	4.2	3.4	2C3	3.90		.11	1.65	4.00			7	26	33						
141.0	145.5	10679	4.5	4.4	2C3	4.10		.20	2.38	10.00			7	28	36						
145.5	150.5	10680	5.0	4.7	2D3	3.90		1.86	2.89	38.00			5	26	31						
150.5	155.0	10681	4.5	3.2	2E1	4.40		.30	1.27	6.00			4	35	39						
155.0	158.6	10682	3.6	3.5	2E1	4.30		.05	1.18	2.00			3	36	40						
158.6	162.0	10683	3.4	3.2	2E4	4.20		.35	1.24	2.00			3	35	38						
162.0	167.5	10684	5.5	5.3	2E4	4.50		3.54	5.94	8.00			3	34	38						
167.5	173.0	10685	5.5	4.8	2A4	4.50		2.86	6.41	8.00			3	34	37						
173.0	179.0	10686	6.0	3.8	2A4	3.70		3.59	8.93	18.00			2	20	22						
179.0	184.1	10687	5.1	4.2	2A4	3.60		6.27	12.50	44.00			3	13	16						
184.1	190.0	10688	5.9	4.9	2A4	4.00		4.58	11.20	24.00			1	26	28						
190.0	194.7	10689	4.7	3.5	2C0	3.00		.71	1.60	40.00			2	8	11						
194.7	200.8	10690	6.1	4.7	2C0	3.10		.50	1.71	8.00			3	9	13						
200.8	206.7	10691	5.9	5.1	2C0	3.10		.90	2.78	16.00			2	11	14						
206.7	211.0	10692	4.3	4.2	2C0	2.80		.96	1.83	14.00			2	2	4						
211.0	216.0	10693	5.0	3.3	2C0	2.90		.13	.18	4.00			3	5	8						

DDH: 86F-21 UTM-N: 9420.2 UTM-E: 14923.7 UTM-ELEV: 3708.4 TOTAL DEPTH: 299.0 SECTION: 119+070
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 315 DHD CALC: 1 SS CALC: 1

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %
10.0	16.0	34751	6.0	5.4	2C38	3.90		.48	1.38	10.00			1	30	32					
16.0	21.0	34752	5.0	4.7	2C38	4.10		.75	1.02	8.00			4	30	35					
21.0	26.0	34753	5.0	4.7	2C38	4.10		.25	1.58	10.00			6	28	35					
26.0	31.0	34754	5.0	4.8	2C38	4.20		.37	1.19	4.00			4	30	35					
31.0	36.0	34755	5.0	4.9	2C38	4.30		.06	.56	4.00			4	35	39					
36.0	41.0	34756	5.0	4.7	2C38	4.40		.49	.37	6.00			2	37	40					
41.0	43.0	34757	2.0	1.8	2C38	3.70		.87	1.03	4.00				28	29					
43.0	47.0	10613	4.0	3.8	2C3	3.20		.71	.95	8.00			2	15	17					
47.0	52.3	34758	5.3	5.3	2A0	3.70		.70	1.22	12.00			2	22	25					
52.3	62.2	10614	9.9	7.6	1D4	3.00		.83	.13	38.00			3	2	5					
62.2	67.0	34759	4.8	4.6	2C3	3.70		1.11	2.09	14.00			2	23	26					
67.0	71.5	34760	4.5	4.2	2C3	3.90		.79	1.34	8.00			1	25	27					
71.5	75.5	34761	4.0	3.8	2C3	4.00		.15	.40	4.00				30	31					
75.5	80.5	34762	5.0	4.7	2C3	3.90		.04	1.42	2.00			1	30	32					
80.5	85.5	34763	5.0	4.9	2E81	4.50		.14	1.15	2.00			6	30	37					
85.5	90.5	34764	5.0	4.8	2E81	3.80		.63	.74	4.00			7	28	36					
90.5	95.0	10610	4.5	3.9	2E1	3.90		.76	2.07	4.00			1	28	29					
95.0	99.5	34765	4.5	4.3	2E1	3.70		.70	1.08	6.00			1	30	31					
99.5	104.0	34766	4.5	4.2	2E1	4.60		1.03	.55	14.00				35	35					
104.0	108.5	34767	4.5	4.4	2E1	3.90		3.09	.31	34.00				29	30					
108.5	114.0	10612	5.5	4.9	BXA	3.70		3.95	7.10	22.00			2	20	22					
114.0	121.7	34768	7.7	7.2	2A3	3.90		.96	1.36	12.00			1	24	25					
121.7	126.7	34769	5.0	4.7	2C38	4.10		.50	1.42	2.00			3	32	35					
126.7	131.7	34770	5.0	4.9	2C38	3.90		.34	1.36	2.00			7	24	31					
131.7	136.3	34771	4.6	4.5	2C38	4.10		.12	.37	4.00			5	31	36					
136.3	140.5	34772	4.2	3.9	2C38	4.00		.15	1.33	2.00			1	31	33					
140.5	145.5	34773	5.0	4.6	2C38	4.00		.10	1.81	2.00			2	30	32					
145.5	151.2	34774	5.7	5.5	2C38	4.20		.22	1.38	2.00			3	27	30					
151.2	155.2	10615	4.0	3.6	2E18	4.10		.67	1.97	6.00			4	28	32					
155.2	161.0	34775	5.8	5.3	2D3	4.20		.59	1.80	4.00			2	27	30					
161.0	166.0	34776	5.0	4.8	2C3	3.60		.13	2.21	4.00			1	24	26					
166.0	174.0	34777	8.0	7.1	2C3	4.00		2.50	6.00	8.00			2	24	27					
174.0	177.0	34778	3.0	2.1	2D5	4.20		6.79	6.16	74.00			2	34	36					
177.0	182.0	34779	5.0	4.4	2D5	3.80		1.07	3.20	30.00			1	18	20					
182.0	186.0	34780	4.0	3.5	2D5	3.40		2.48	5.88	24.00			3	12	16					
186.0	190.0	34781	4.0	3.3	2C5	3.30		1.57	2.10	36.00			1	5	7					
190.0	194.5	34782	4.5	4.2	2D5	2.90		1.67	3.07	22.00			2	3	6					
194.5	200.0	34783	5.5	4.0	2D5	2.90		1.19	3.02	20.00			3	6	10					
200.0	205.0	34784	5.0	4.8	2C5	3.10		1.32	2.05	18.00			3	8	12					
205.0	210.0	34785	5.0	4.9	2C5	3.20		1.04	1.72	16.00			3	9	13					
210.0	215.0	34786	5.0	4.7	2C5	3.10		2.16	1.55	42.00			2	3	5					
215.0	219.0	34787	4.0	3.5	2A4	3.30		5.00	7.42	44.00			3	15	19					
219.0	231.3	10611	12.3	10.2	2D5	2.90		1.92	5.05	32.00			4	10	15					
231.3	237.0	34788	5.7	5.4	2D5	2.80		1.05	3.65	26.00			2	2	5					
237.0	242.0	34789	5.0	4.4	2D5	2.80		.85	3.46	20.00			1	1	2					
242.0	247.0	34790	5.0	4.6	2C5	2.80		.71	2.82	16.00			1	2	3					
247.0	252.0	34791	5.0	4.9	2D5	2.90		2.00	3.96	36.00			2	3	5					
252.0	257.0	34792	5.0	4.7	2D5	2.90		.32	3.55	24.00			1	4	6					
257.0	264.0	34793	7.0	6.3	2D5	2.90		1.52	4.43	26.00			2	3	5					
264.0	269.0	34794	5.0	4.1	2C5	2.90		.84	3.13	22.00			1	2	4					
269.0	272.0	34795	3.0	2.8	2D5	2.90		1.63	3.47	24.00			2	3	6					

DDH: 86F-21 UTM-N: 9420.2 UTM-E: 14923.7 UTM-ELEV: 3708.4 TOTAL DEPTH: 299.0 SECTION: 119+070
RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 315 DHD CALC: 1 SS CALC: 1

-----DEPTHS---							-----ASSAYS-----													
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
272.0	277.5	34796	5.5	4.6	205	2.90	.27	.28	10.00			2	3	6						
277.5	280.7	34797	3.2	2.9	1D419	2.90	.62	1.20	26.00			3	3	6						
280.7	289.0	10616	8.3	7.5	1D419	2.80	1.03	1.92	8.00			2	1	4						
289.0	296.5	34798	7.5	7.1	1D419	2.90	2.11	.97	22.00			2	3	6						
296.5	299.0	34799	2.5	2.3	1D419	3.00	3.45	1.85	40.00			4	7	11						

DDH: 86F-22 UTM-N: 9260.3 UTM-E: 14657.5 UTM-ELEV: 3708.4 TOTAL DEPTH: 327.0 SECTION: 119+000
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 315 DHD CALC: 1 SS CALC: 1

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %
104.3	108.2	10629	3.9	3.7	1H0	3.00		1.98	3.28	44.00			2	3	5					
108.2	110.4	10630	2.2	2.1	2G74	4.30		4.27	6.49	94.00			20	10	30					
110.4	115.0	10631	4.6	3.9	1H0	3.20		2.82	2.26	44.00			7	10	18					
115.0	117.5	10632	2.5	2.4	2G7	4.00		3.73	6.00	68.00			12	16	28					
117.5	123.0	10633	5.5	5.3	1H0	4.40		2.46	3.80	46.00			8	12	20					
123.0	131.2	10634	8.2	7.9	1H0	3.00		1.37	.95	18.00			5	3	9					
131.2	135.0	10635	3.8	3.7	2G74	4.30		5.74	7.63	64.00			4	17	22					
135.0	141.5	10636	6.5	6.1	2E4	4.50		3.44	2.90	48.00			6	29	35					
141.5	146.8	10637	5.3	5.0	2E0	4.50		1.33	1.15	14.00			5	28	34					
146.8	152.2	10638	5.4	5.2	2E0	4.60		1.13	.40	24.00			10	32	42					
152.2	156.5	10639	4.3	4.2	2E4#	4.50		5.11	5.51	22.00			12	26	38					
156.5	160.8	10640	4.3	4.1	2E4#	4.40		4.12	4.12	26.00			13	24	37					
160.8	165.2	10641	4.4	4.3	2E#	4.30		.45	.20	6.00			9	31	41					
165.2	170.1	10642	4.9	4.7	2E84	4.70		2.23	2.69	30.00			3	37	41					
170.1	174.5	10643	4.4	4.2	2E80	4.70		2.06	1.62	50.00			7	34	41					
174.5	179.0	10644	4.5	4.5	2E80	4.40		1.89	.79	36.00			10	30	41					
179.0	183.3	10645	4.3	4.1	2E84	4.40		2.83	2.10	48.00			12	27	40					
183.3	188.7	10646	5.4	5.0	2E84	4.40		2.38	3.17	34.00			14	28	42					
188.7	192.0	10647	3.3	2.9	2E4	4.80		3.18	4.56	28.00			2	35	38					
192.0	196.0	10648	4.0	3.6	2E0	4.10		.85	2.39	18.00			4	29	33					
196.0	199.5	10649	3.5	2.5	2E4	4.60		4.18	5.47	32.00			3	32	36					
199.5	203.7	10650	4.2	3.6	2E4	4.70		2.57	5.33	24.00			2	35	38					
203.7	206.0	10652	2.3	1.8	2E4	4.70		5.21	5.96	32.00				36	37					
206.0	209.6	10617	3.6	3.4	2D5	3.70		3.77	4.11	34.00			3	20	23					
209.6	214.4	10601	4.8	4.5	2D59	2.90		1.03	4.21	24.00			2	2	5					
214.4	218.7	10602	4.3	3.9	2C59	3.10		.33	2.41	10.00			6	9	16					
218.7	223.7	10603	5.0	4.8	2C59	3.10		1.07	2.07	22.00			6	8	14					
223.7	228.5	10604	4.8	4.8	2C59	2.90		.84	1.63	16.00			1	2	4					
228.5	232.6	10626	4.1	3.8	2C0	2.90		.71	.72	11.00			2	2	5					
232.6	236.5	10627	3.9	3.1	1CD4	2.90		.03	.10				3	1	4					
236.5	240.3	10605	3.8	3.3	1CD4	2.90		.03	.03	4.00			3		4					
240.3	244.7	10606	4.4	4.2	1CD4	2.90		.02	.12	2.00			5	2	7					
244.7	248.8	10607	4.1	3.8	1CD4	2.80		.06	.05	4.00			3	1	4					
248.8	254.5	10628	5.7	5.6	2C0	2.90		.83	1.07	10.00			2	2	4					
254.5	258.0	10608	3.5	3.2	2A0	2.90		.68	2.91	16.00			4	4	8					
258.0	262.0	10609	4.0	3.8	2A0	2.90		.75	2.23	16.00			3	1	5					
262.0	267.0	10618	5.0	4.8	2C0	2.70		.53	1.65	8.00			2	2	4					
267.0	272.0	10619	5.0	4.7	2C0	2.80		1.11	1.24	12.00			2	3	6					
272.0	278.5	10620	6.5	5.9	2A70	2.90		.41	1.30	8.00			3	3	7					
278.5	284.0	10621	5.5	5.4	2A70	2.80		.80	1.48	16.00			4		5					
284.0	290.7	10622	6.7	6.4	2A70	2.90		.52	1.55	12.00			3	1	5					
290.7	297.0	10623	6.3	5.9	2A70	2.80		.66	2.31	18.00			3	2	5					
297.0	302.0	10624	5.0	4.8	2DJ4	3.90		33.60	2.43	276.00			2	1	4					
302.0	306.0	10625	4.0	3.7	2L14	2.80		.89	1.59	17.00			2	1	3					

DDH: 86F-23 UTM-N: 9181.7 UTM-E: 14980.9 UTM-ELEV: 3705.1 TOTAL DEPTH: 387.0 SECTION: 121+000
RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 315 DHD CALC: 1 SS CALC: 1

-----DEPTHS----		-----ASSAYS-----																		
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
106.0	111.0	04967	5.0	4.9 2E4	4.10		3.58	6.30	57.00			2	25	27						
111.0	116.0	04968	5.0	4.7 2E4	4.70		9.96	8.75	167.00			4	22	26						
116.0	122.5	04969	6.5	4.4 2E4	3.70		2.66	10.90	19.00			3	14	17						
122.5	127.0	04970	4.5	4.3 2E4	3.90		5.02	10.10	55.00			4	24	29						
127.0	132.0	04971	5.0	4.9 2A3	3.80		.93	1.09	11.00			2	24	27						
132.0	136.5	04972	4.5	4.1 2E0	4.60		.25	.36	8.00			2	40	42						
136.5	140.0	04973	3.5	3.5 2E0	4.70		.64	.86	8.00			1	40	41						
140.0	144.5	04974	4.5	4.1 2A34	3.90		1.32	4.99	9.00			1	23	24						
144.5	148.7	04975	4.2	4.0 2A34	3.80		2.10	6.11	19.00			1	21	23						
148.7	152.7	04976	4.0	3.8 2A3	3.80		.48	1.80	11.00				30	31						
152.7	156.7	04977	4.0	3.9 2A3	3.90		.50	1.30	9.00			1	29	30						
156.7	161.5	04978	4.8	4.5 2E81	4.20		.57	2.11	6.00			6	30	36						
161.5	166.5	04979	5.0	4.3 2E81	4.20		1.31	2.36	8.00			8	30	39						
166.5	170.8	04980	4.3	3.0 2E81	4.20		.71	1.89	8.00			7	28	35						
170.8	177.0	04981	6.2	5.8 2E1	4.10		.08	.61	9.00				35	35						
177.0	183.0	04982	6.0	4.2 2E1	3.80		.59	.72	9.00			1	28	29						
183.0	189.0	04984	6.0	5.6 2D34	3.40		3.34	8.62	20.00			2	14	17						
189.0	193.2	04983	4.2	3.8 2C35	3.40		.90	2.57	10.00			5	18	24						
193.2	198.0	04985	4.8	4.5 2C35	3.60		.38	.79	20.00			9	21	30						
198.0	204.0	04986	6.0	5.7 2D45	3.80		3.38	5.94	20.00			5	7	13						

DDH: 86F-24 UTM-N: 9051.2 UTM-E: 14853.9 UTM-ELEV: 3710.2 TOTAL DEPTH: 391.0 SECTION: 121+000
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 315 DHD CALC: 1 SS CALC: 1

-----DEPTHS-----							-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.	
130.6	135.0	10738	4.4	4.2	2D0	3.50		2.81	5.81	56.00				7	15	23						
135.0	142.3	10739	7.3	5.8	2CD	2.90		.46	1.05	16.00				3	6	9						
142.3	146.0	10740	3.7	3.5	2G4	4.50		4.81	6.58	72.00				1	20	22						
146.0	150.0	10741	4.0	3.7	2F64	4.70		6.24	5.45	76.00				2	27	30						
150.0	160.6	10742	10.6	4.5	2F64	4.60		9.23	8.61	128.00				4	18	23						
160.6	166.5	10743	5.9	5.5	2E4	4.70		2.48	1.80	32.00				1	40	42						
166.5	171.5	10744	5.0	4.7	2EG4	4.70		4.69	6.56	64.00					33	34						
171.5	175.5	10745	4.0	3.5	2E4	4.70		3.53	4.97	44.00				2	35	37						
175.5	180.0	10746	4.5	3.6	2E48	4.80		3.16	3.84	32.00				4	30	34						
180.0	184.0	10747	4.0	1.5	2E48	4.80		3.80	4.17	38.00				2	37	40						
184.0	192.5	10748	8.5	3.3	2E4	4.60		2.90	3.67	34.00				1	39	41						
192.5	199.5	10749	7.0	6.3	2E0	4.50		1.26	.77	20.00					39	40						
199.5	205.0	10750	5.5	4.7	2E0	4.60		1.06	.90	14.00					41	41						
205.0	211.0	04987	6.0	4.6	2E4	4.60		2.27	3.49	26.00				1	35	37						
211.0	217.0	04988	6.0	5.6	2E14	4.70		3.35	2.76	36.00				1	39	40						
217.0	221.5	04989	4.5	4.3	2E01	4.60		1.28	.45	16.00					38	38						
221.5	226.3	04990	4.8	4.1	2E14	4.70		2.97	3.93	34.00				1	36	37						
226.3	232.0	04991	5.7	5.6	2D3	4.40		3.07	5.72	48.00				4	29	34						
232.0	238.0	04992	6.0	5.9	2D3	4.40		2.07	2.29	16.00				5	34	40						
238.0	243.5	04993	5.5	5.1	2C3	3.90		1.20	1.10	20.00				1	30	32						
243.5	247.0	04994	3.5	3.5	2E80	4.20		.47	.85	6.00				10	31	41						
247.0	250.5	04995	3.5	3.3	2E1	4.50		.04	1.59	4.00				3	36	40						
250.5	255.5	04996	5.0	4.1	2E1	3.70		2.91	.51	80.00				5	20	26						
255.5	259.5	04997	4.0	3.8	2E1	4.30		.04	1.11	4.00				2	36	39						
259.5	264.3	04998	4.8	4.5	2E1	4.20		.55	1.38	6.00				3	33	37						
264.3	271.0	04999	6.7	6.6	2E4	4.50		5.81	8.21	16.00				6	27	34						
271.0	275.0	05000	4.0	3.6	2E1	4.20		.31	1.59	6.00				4	31	36						
275.0	279.0	43051	4.0	3.3	2E1	4.10		.79	.71	10.00				4	31	36						
279.0	283.0	43052	4.0	3.1	2E1	4.00		.75	1.18	6.00				3	31	34						
283.0	287.0	43053	4.0	3.0	2E1	4.10		.69	2.55	4.00				5	31	36						
287.0	291.0	43054	4.0	3.3	2E48	4.30		4.35	8.09	12.00				4	28	33						
291.0	295.0	43055	4.0	3.8	2E48	4.20		2.88	6.31	10.00				4	29	33						
295.0	299.0	43056	4.0	3.7	2E48	4.50		4.02	8.37	10.00				6	24	31						
299.0	302.0	43057	3.0	2.2	2E48	4.20		1.45	4.23	6.00				6	29	36						
302.0	306.5	43058	4.5	3.8	2E08	4.50		1.09	2.20	6.00				5	34	40						
306.5	311.0	43059	4.5	4.2	2E08	4.20		1.14	1.93	8.00				6	30	37						
311.0	315.0	43060	4.0	2.8	2E08	4.40		.65	1.71	8.00				7	32	39						
315.0	319.5	43061	4.5	3.9	2E08	4.40		.87	1.80	8.00				6	33	40						
319.5	324.0	43062	4.5	4.2	2E08	4.20		.22	1.14	6.00				7	29	36						
324.0	327.0	43063	3.0	.9	BXA	2.90		.14	.47	8.00				6	6	12						
327.0	331.5	43064	4.5	4.1	2E4	4.80		4.49	8.39	20.00				1	35	36						
331.5	335.5	43065	4.0	3.7	2E0	4.40		5.02	9.28	26.00				2	29	31						
335.5	339.5	43066	4.0	3.9	2A34	4.50		5.21	10.30	26.00				1	29	31						
339.5	344.0	43067	4.5	4.1	2A34	3.70		3.86	9.52	24.00				2	19	21						
344.0	348.8	43068	4.8	4.4	2A34	3.50		1.40	5.76	20.00				2	18	21						
348.8	351.5	43069	2.7	2.4	2A34	3.50		4.87	10.10	26.00				3	11	15						
351.5	355.0	43070	3.5	3.2	2A34	4.10		3.91	9.45	20.00				2	24	27						
355.0	359.3	43071	4.3	4.0	2A34	3.50		2.23	6.50	14.00				1	17	19						
359.3	363.5	43072	4.2	3.9	2A34	3.40		4.32	12.80	24.00				2	11	13						
363.5	367.0	43073	3.5	3.5	2J732	3.90		8.27	20.70	34.00				10	8	18						
367.0	373.0	43074	6.0	5.1	2D5	3.10		1.54	5.29	16.00				5	8	13						

DDH: 86F-25 UTM-N: 8979.0 UTM-E: 14772.6 UTM-ELEV: 3713.0 TOTAL DEPTH: 411.0 SECTION: 121+000
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 315 DHD CALC: 1 SS CALC: 1

---DEPTHS---		-----ASSAYS-----																		
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
167.5	170.0	10694	2.5	2.4	2D0	3.10	2.02	3.39	36.00			5	9	15						
170.0	175.5	10695	5.5	3.3	1D4	2.80	.47	.27	10.00			2	2	5						
175.5	181.0	10696	5.5	3.1	2LE34	3.70	4.31	3.97	74.00			11	15	26						
181.0	185.0	10697	4.0	1.7	2LE34	4.30	5.30	4.95	84.00			14	21	36						
185.0	189.7	10698	4.7	2.4	2LE34	3.50	2.97	2.38	44.00			8	17	25						
189.7	195.7	10699	6.0	5.9	2G4	4.10	5.00	5.01	72.00			2	21	23						
195.7	200.0	10700	4.3	4.1	2E4L	3.60	.87	1.01	30.00			5	23	28						
200.0	207.8	10701	7.8	7.4	1H4	2.90	.72	.31	38.00			7	4	12						
207.8	212.5	10702	4.7	4.4	2E0	4.10	2.44	1.23	32.00			1	36	38						
212.5	217.6	10703	5.1	5.0	2E4	4.60	1.69	2.40	22.00			1	38	40						
217.6	221.6	10704	4.0	3.7	2E4	4.70	2.57	3.91	22.00				41	42						
221.6	226.0	10705	4.4	3.9	2E4	4.30	4.78	3.40	28.00			1	30	32						
226.0	232.5	10706	6.5	5.7	2E4	4.60	3.17	3.17	32.00			4	36	40						
232.5	239.8	10707	7.3	6.8	2C3	4.00	2.18	.17	34.00				33	33						
239.8	244.6	10708	4.8	4.7	2E0	4.60	1.54	.86	24.00			2	40	42						
244.6	250.7	10709	6.1	5.9	2E0	4.80	1.47	.75	20.00			1	39	41						
250.7	258.0	10710	7.3	6.9	2E84	4.60	2.93	2.30	44.00			4	36	40						
258.0	264.0	10711	6.0	5.8	2E84	4.50	3.15	3.95	36.00			5	32	38						
264.0	268.8	10712	4.8	4.4	2E8	4.40	1.14	2.78	14.00			7	31	39						
268.8	273.0	10713	4.2	3.5	2E0	4.40	.92	1.12	8.00			1	38	39						
273.0	278.0	10714	5.0	4.8	2E4	4.80	5.35	8.18	44.00			1	36	37						
278.0	282.0	10715	4.0	4.0	2E0	4.50	.13	.14	6.00				39	40						
282.0	286.7	10716	4.7	2.1	2E0	4.50	2.06	1.88	16.00			1	37	39						
286.7	290.0	10717	3.3	2.3	2E8	4.50	1.63	1.95	14.00			6	34	41						
290.0	295.0	10718	5.0	4.2	2E8	4.00	1.46	2.12	12.00			2	31	34						
295.0	299.0	10719	4.0	3.9	2E84	4.50	2.35	5.33	16.00			6	32	39						
299.0	303.0	10720	4.0	3.8	2E8	4.60	.55	.66	6.00			6	37	44						
303.0	306.5	10721	3.5	2.2	2E8	4.60	1.45	2.24	12.00			8	33	41						
306.5	310.0	10722	3.5	3.2	2E4	4.60	2.10	3.00	24.00			5	35	41						
310.0	315.0	10723	5.0	3.9	2E4	4.70	3.00	6.15	20.00			4	33	37						
315.0	319.0	10724	4.0	3.4	2E4	4.50	2.70	5.38	20.00			1	36	38						
319.0	324.0	10725	5.0	3.6	2E4	4.80	3.46	5.21	20.00				37	38						
324.0	330.0	10726	6.0	3.7	2E4	4.70	2.00	3.48	14.00			1	40	41						
330.0	335.0	10727	5.0	4.1	2E4	4.60	4.90	9.35	22.00			1	33	35						
335.0	339.0	10728	4.0	3.7	2E4	4.60	3.45	6.85	16.00			2	32	34						
339.0	343.5	10729	4.5	4.2	2E4	4.40	4.16	8.59	20.00			2	32	35						
343.5	348.0	10730	4.5	2.3	2C5	3.30	1.27	1.87	18.00			6	13	20						
348.0	355.0	10731	7.0	6.8	2C5	3.00	1.25	2.73	24.00			2	4	6						
355.0	361.3	10732	6.3	5.8	2D5	3.00	2.11	2.06	32.00			2	2	4						
361.3	364.0	10733	2.7	2.6	2C05	3.30	.25	.43	8.00			10	13	24						
364.0	367.0	10734	3.0	2.9	2D75	3.60	1.63	4.34	24.00			13	15	28						
367.0	374.0	10735	7.0	6.8	2C5	3.10	.40	2.09	10.00			3	11	15						
374.0	378.5	10736	4.5	4.5	2C0	2.80	.68	1.44	16.00			1	4	6						
378.5	383.0	10737	4.5	4.4	2C0	2.90	.81	2.12	16.00			3	3	7						

**THIS REPORT WAS REQUESTED BY: LEEP

GEOLOGY

AT: 14:08:17