

VANAL

PCXPLOR

VANGORDA X-SECTION

08W
06W

10548.64

* TYPE


PLOTMODE

NORTHINGS

EASTINGS

-20
470
-50
315
18500

NAME	NORTHINGS	EASTINGS	ROW	DESCRIPTION
04 W	10487.68		11	
03 W	10457.20		13	
02 W	10426.72	9797.50 ↔ 10247.50	15	
01 W	10396.24		17	
00	10365.76		19	
01 E	10335.28		21	
02 E	10304.80		23	
03 E	10274.32		25	
04 E	10243.84		27	
05 E	10213.36	9797.50 EASTINGS left	29	
06 E	10182.88		31	
07 E	10152.40	10247.50 EASTINGS right		
08 E	10121.92		35	
09 E	10091.44	1205 top elev		
10 E	10060.96	910 bottom elev	39	
11 E	10030.48	15.24 projection	41	
12 E	10000.00		43	NO ← 1 reference grid
13 E	* 9969.52			1 grid character size
14 E	9939.04		47	100 Easting interval
15 E	* 9908.56		49	1 linestyle
16 E	9878.08		51	3 - green - east grid line
17 E	9847.6		53	100 North interval
18 E	9817.12		55	1 linestyle
19 E	9786.64		57	3 green North grid line
20 E	9756.16		59	50 elev interval
21 E	9725.68		61	1 linestyle
22 E	9695.20		63	3 green elevs
23 E	* 9664.72			1 black - box face
24 E	9634.24		67	1 black drill hole trace
25 E	* 9603.76			1 ← 2 fields from table
26 E	9573.28		71	→ [] - field name
27 E	* 9542.80			X [] - field name
28 E	9512.32		75	X 3 elevation
29 E	* 9481.84			1 black - fields
30 E	9451.36			2 ← 1 collar
31 E	* 9420.88			Yes - left hand side
32 E	* 9390.40			3 table no.



VANGORDA DEPOSIT
VERTICAL CROSS SECTION
04 W

[] - field
[] - field

SECTION 14E

POLYGON	TYPE	DR HOLE	LENGTH	WIDTH	THICKNESS
14E1 ✓	A	88V50	60.96	13	2.0
14E2 ✓	A	P54V040	60.96	15	3
14E3 ✓	A	88V09	60.96	15	3.5
14E4 ✓	A	P55V098	45.72	15	1.5
14E5 ✓	B	P55V098	45.72	15	4
14E6 ✓	A	P55V098	45.72	15	1.5
14E7 ✓	A	88V08	60.96	15	2.5
14E8 ✓	A	88V08	60.96	15	13
14E9 ✓	A	88V08	60.96	15	7
14E10 ✓	A	88V08	60.96	15	2
14E11 ✓	A	P54V052	30.48	16	6
14E12 ✓	A	P54V052	30.48	16	3
14E13 ✓	A	87V02	45.72	15.5	16
14E14 ✓	A	P55V097	45.72	14	11
14E15 ✓	A	P55V097	45.72	14	3
14E16 ✓	A	87V01	76.2	16	16
14E17 ✓	A	P54V056	60.96	15	4.5
14E18 ✓	B	88V08	60.96	15	2

SECTION 15E

Polygon	Type	DD HOLE	LENGTH	WIDTH	THICKNESS
15E1 ✓	A	88V10	30.48	32	3.0
15E2 ✓	A	88V10	30.48	32	4.5
15E3 ✓	B	88V16	30.48	30	2.5
15E4 ✓	A	88V16	30.48	30	3.0
15E5 ✓	A	88V13	30.24	22.5	10.0

SECTION 12E

POLYGON	TYPE	ODHOLE	LENGTH	WIDTH	THICKNESS
12E1 ✓	A	88V48	60.96	16	
12E2 ✓	A	88V06	60.96	16	9
12E3 ✓	B	88V06	60.96	16	11
12E4 ✓	A	88V63	60.96	15	2.5
12E5 ✓	B	88V63	60.96	15	3.0
12E6 ✓	B	88V63	60.96	15	2.0
12E7 ✓	A	79V057R	60.96	22	2.0
12E8 ✓	A	79V312	60.96	30	1.5
12E9 ✓	A	79V309R	60.96	30	4.0
12E10 ✓	B	79V309	60.96	30	4.5
12E11 ✓	A	79V309	60.96	30	2.0
12E12 ✓	A	79V309	60.96	30	6.0
12E13 ✓	A	79V063R	60.96	30	13
12E14 ✓	A	79V309	60.96	30	1.5

954

SECTION 13E

POLYGON		TYPE	ODHOLE	LENGTH	WIDTH	THICKNESS
'3E1	✓	A	88V05	30.48	17	16.5
13E2	✓	A	88V05	30.48	17	4.0

CURRAGH RESOURCES INC.
 VANGORDA PROJECT, FARO, YUKON

DRILLHOLE COMPOSITES SECTION: 12_08 POLYGON: 12E1

hole	from	to	interval	rock code	Pb+Zn	Pb(%)	Zn(%)	Ag(g/t)	Au(g/t)	S.G.
88V-48	51.2	52.4	1.2	42	5.34	3.16	2.18	48.0	0.96	3.90
88V-48	52.4	53.4	1.0	42	7.40	4.81	2.59	88.0	1.71	3.10
88V-48	53.4	54.7	1.3	42	6.90	4.21	2.69	78.0	0.48	3.20

SECTION: 12_08 POLYGON: 12E1

COMPOSITED ASSAY OF SELECTED INTERVALS

S.G. and length weighted composites:

number of samples	from (m)	to (m)	interval (m)	Pb+Zn (%)	Pb (%)	Zn (%)	Ag (g/t)	Au (g/t)	S.G.
3	51.2	54.7	3.5	6.42	3.95	2.46	68.8	0.99	3.41

Length weighted composites:

number of samples	from (m)	to (m)	interval (m)	Pb+Zn (%)	Pb (%)	Zn (%)	Ag (g/t)	Au (g/t)	S.G.
3	51.2	54.7	3.5	6.51	4.02	2.49	70.6	1.00	3.41

CURRAGH RESOURCES INC.
VANGORDA PROJECT, FARO, YUKON

DRILLHOLE COMPOSITES SECTION: 12_08 POLYGON: 12E2

hole	from	to	interval	rock code	Pb+Zn	Pb(%)	Zn(%)	Ag(g/t)	Au(g/t)	S.G.
88V-06	52.4	53.6	1.2	62	8.90	4.43	4.47	60.0	0.55	4.50
88V-06	53.6	54.8	1.2	62	7.03	3.79	3.24	54.0	0.75	4.20
88V-06	54.8	55.9	1.1	62	8.94	4.59	4.35	60.0	0.75	4.30
88V-06	55.9	57.2	1.3	62	8.92	4.62	4.30	56.0	0.82	4.80
88V-06	57.2	58.5	1.3	62	8.73	4.16	4.57	52.0	1.30	4.60
88V-06	58.5	59.7	1.2	62	7.90	3.67	4.23	46.0	0.62	4.60
88V-06	59.7	61.3	1.6	62	7.31	3.59	3.72	46.0	0.75	4.50
88V-06	61.3	62.3	1.0	62	6.00	2.91	3.09	44.0	0.69	4.20

SECTION: 12_08 POLYGON: 12E2

COMPOSITED ASSAY OF SELECTED INTERVALS

S.G. and length weighted composites:

number of samples	from (m)	to (m)	interval (m)	Pb+Zn (%)	Pb (%)	Zn (%)	Ag (g/t)	Au (g/t)	S.G.
8	52.4	62.3	9.9	8.01	3.99	4.02	52.1	0.79	4.48

Length weighted composites:

number of samples	from (m)	to (m)	interval (m)	Pb+Zn (%)	Pb (%)	Zn (%)	Ag (g/t)	Au (g/t)	S.G.
8	52.4	62.3	9.9	7.99	3.98	4.01	52.1	0.79	4.48

CURRAGH RESOURCES INC.
VANGORDA PROJECT, FARO, YUKON

DRILLHOLE COMPOSITES SECTION: 12_0E POLYGON: 12E3

hole	from	to	interval	rock code	Pb+Zn	Pb(%)	Zn(%)	Ag(g/t)	Au(g/t)	S.G.
88V-06	62.3	63.6	1.3	22	6.93	3.31	3.62	48.0	0.55	3.10
88V-06	63.6	65.1	1.5	22	3.51	2.64	0.87	38.0	0.27	3.00
88V-06	65.1	66.6	1.5	22	4.60	2.77	1.83	39.0	0.62	3.00
88V-06	66.6	67.8	1.2	22	10.17	5.53	4.64	77.0	0.48	3.00
88V-06	67.8	69.0	1.2	22	8.38	5.17	3.21	198.0	0.55	3.10
88V-06	69.0	70.3	1.3	22	7.06	4.24	2.82	69.0	0.55	3.20
88V-06	70.3	71.8	1.5	22	8.44	4.57	3.87	75.0	0.62	3.10
88V-06	71.8	73.2	1.4	22	8.26	3.45	4.81	55.0	0.55	3.10
88V-06	73.2	74.7	1.5	22	5.80	2.78	3.02	47.0	0.62	3.30

SECTION: 12_0E POLYGON: 12E3

COMPOSITED ASSAY OF SELECTED INTERVALS-----

S.G. and length weighted composites:

number of samples	from (m)	to (m)	interval (m)	Pb+Zn (%)	Pb (%)	Zn (%)	Ag (g/t)	Au (g/t)	S.G.
9	62.3	74.7	12.4	6.90	3.76	3.15	69.2	0.54	3.10

Length weighted composites:

number of samples	from (m)	to (m)	interval (m)	Pb+Zn (%)	Pb (%)	Zn (%)	Ag (g/t)	Au (g/t)	S.G.
9	62.3	74.7	12.4	6.90	3.76	3.14	69.2	0.53	3.10

CURRAGH RESOURCES INC.
VANGORDA PROJECT, FARO, YUKON

DRILLHOLE COMPOSITES SECTION: 12_OR POLYGON: 12R4

hole	from	to	interval	rock code	Pb+Zn	Pb(%)	Zn(%)	Ag(g/t)	Au(g/t)	S.G.
88V-63	42.1	42.6	0.5	62	13.38	4.36	9.02	63.0	0.34	3.40
88V-63	42.6	43.4	0.8	62	8.38	3.17	5.21	48.0	0.41	3.50
88V-63	43.4	44.3	0.9	62	7.54	3.11	4.43	48.0	0.55	3.70

SECTION: 12_OR POLYGON: 12R4

COMPOSITED ASSAY OF SELECTED INTERVALS

S.G. and length weighted composites:

number of samples	from (m)	to (m)	interval (m)	Pb+Zn (%)	Pb (%)	Zn (%)	Ag (g/t)	Au (g/t)	S.G.
3	42.1	44.3	2.2	9.11	3.40	5.71	51.3	0.45	3.56

Length weighted composites:

number of samples	from (m)	to (m)	interval (m)	Pb+Zn (%)	Pb (%)	Zn (%)	Ag (g/t)	Au (g/t)	S.G.
3	42.1	44.3	2.2	9.17	3.42	5.76	51.4	0.45	3.56

CURRASH RESOURCES INC.
 VANGORDA PROJECT, FARGO, YUKON

DRILLHOLE COMPOSITES SECTION: 12_0E POLYGON: 12E5

hole	from	to	interval	rock code	Pb+Zn	Pb(%)	Zn(%)	Ag(g/t)	Au(g/t)	S.G.
88V-63	56.3	57.7	1.4	22	7.20	2.33	4.87	39.0	0.41	3.00
88V-63	57.7	59.3	1.6	22	6.09	2.47	3.62	38.0	0.55	3.10

SECTION: 12_0E POLYGON: 12E5

COMPOSITED ASSAY OF SELECTED INTERVALS

S.G. and length weighted composites:

number of samples	from (m)	to (m)	interval (m)	Pb+Zn (%)	Pb (%)	Zn (%)	Ag (g/t)	Au (g/t)	S.G.
2	56.3	59.3	3	6.60	2.41	4.19	38.5	0.49	3.05

Length weighted composites:

number of samples	from (m)	to (m)	interval (m)	Pb+Zn (%)	Pb (%)	Zn (%)	Ag (g/t)	Au (g/t)	S.G.
2	56.3	59.3	3	6.61	2.40	4.20	38.5	0.48	3.05

CURRAGH RESOURCES INC.
 VANGORDA PROJECT, FARD, YUKON

DRILLHOLE COMPOSITES SECTION: 12_0E POLYGON: 12E6

hole	from	to	interval	rock code	Pb+Zn	Pb(%)	Zn(%)	Ag(g/t)	Au(g/t)	S.G.
88V-63	67.2	68.1	0.9	22	6.68	1.92	4.76	30.0	0.21	3.00
88V-63	68.1	69.2	1.1	22	7.47	2.95	4.52	46.0	0.48	3.30

SECTION: 12_0E POLYGON: 12E6

COMPOSITED ASSAY OF SELECTED INTERVALS

S.G. and length weighted composites:

number of samples	from (m)	to (m)	interval (m)	Pb+Zn (%)	Pb (%)	Zn (%)	Ag (g/t)	Au (g/t)	S.G.
2	67.2	69.2	2	7.13	2.51	4.62	39.2	0.36	3.17

Length weighted composites:

number of samples	from (m)	to (m)	interval (m)	Pb+Zn (%)	Pb (%)	Zn (%)	Ag (g/t)	Au (g/t)	S.G.
2	67.2	69.2	2	7.11	2.49	4.63	38.8	0.36	3.17

CURRAGH RESOURCES INC.
 VANGORDA PROJECT, FARO, YUKON

DRILLHOLE COMPOSITES SECTION: 12_0E POLYGON: 12E7

hole	from	to	interval	rock code	Pb+Zn	Pb(%)	Zn(%)	Ag(g/t)	Au(g/t)	S.G.
79V057R	43.3	45.1	1.8	62	7.99	4.19	3.80	46.0	0.82	4.25

COMPOSITED ASSAY OF SELECTED INTERVALS-----

S.G. and length weighted composites:

number of samples	from (m)	to (m)	interval (m)	Pb+Zn (%)	Pb (%)	Zn (%)	Ag (g/t)	Au (g/t)	S.G.
1	43.3	45.1	1.8	7.99	4.19	3.80	46.0	0.82	4.25

Length weighted composites:

number of samples	from (m)	to (m)	interval (m)	Pb+Zn (%)	Pb (%)	Zn (%)	Ag (g/t)	Au (g/t)	S.G.
1	43.3	45.1	1.8	7.99	4.19	3.80	46.0	0.82	4.25

CURRAGH RESOURCES INC.
 VANGORDA PROJECT, FARD, YUKON

DRILLHOLE COMPOSITES SECTION: 12_0E POLYGON: 12E8

hole	from	to	interval	rock code	Pb+Zn	Pb(%)	Zn(%)	Ag(g/t)	Au(g/t)	S.G.
79V312	41.4	43.0	1.6	32	9.81	3.01	6.80	44.0	0.68	3.40

COMPOSITED ASSAY OF SELECTED INTERVALS

S.G. and length weighted composites:

number of samples	from (m)	to (m)	interval (m)	Pb+Zn (%)	Pb (%)	Zn (%)	Ag (g/t)	Au (g/t)	S.G.
1	41.4	43.0	1.6	9.81	3.01	6.80	44.0	0.68	3.40

Length weighted composites:

number of samples	from (m)	to (m)	interval (m)	Pb+Zn (%)	Pb (%)	Zn (%)	Ag (g/t)	Au (g/t)	S.G.
1	41.4	43.0	1.6	9.81	3.01	6.80	44.0	0.68	3.40

CURRAGH RESOURCES INC.
 VANGORDA PROJECT, FARO, YUKON

DRILLHOLE COMPOSITES SECTION: 12_0E POLYGON: 12E9

hole	from	to	interval	rock code	Pb+Zn	Pb(%)	Zn(%)	Ag(g/t)	Au(g/t)	S.G.
79V309	38.1	39.0	0.9	61	6.32	2.74	3.58	39.0	0.28	4.11
79V309	39.0	40.2	1.2	41	13.31	4.16	9.15	57.0	0.18	4.24
79V309	40.2	41.6	1.4	41	7.46	3.76	3.70	51.0	0.28	4.40

COMPOSITED ASSAY OF SELECTED INTERVALS

S.G. and length weighted composites:

number of samples	from (m)	to (m)	interval (m)	Pb+Zn (%)	Pb (%)	Zn (%)	Ag (g/t)	Au (g/t)	S.G.
3	38.1	41.6	3.5	9.17	3.64	5.53	50.1	0.25	4.27

Length weighted composites:

number of samples	from (m)	to (m)	interval (m)	Pb+Zn (%)	Pb (%)	Zn (%)	Ag (g/t)	Au (g/t)	S.G.
3	38.1	41.6	3.5	9.17	3.63	5.54	50.0	0.25	4.27

CURRAGH RESOURCES INC.
 VANGORDA PROJECT, FARO, YUKON

DRILLHOLE COMPOSITES SECTION: 12_0E POLYGON: 12E10

hole	from	to	interval	rock code	Pb+Zn	Pb(%)	Zn(%)	Ag(g/t)	Au(g/t)	S.G.
79V309	43.2	44.4	1.2	21	19.02	5.75	13.27	52.0	0.25	3.39
79V309	44.4	47.6	3.2	21	14.52	5.71	8.81	54.0	0.21	3.48
79V312	41.4	43.0	1.6	32	9.81	3.01	6.80	44.0	0.68	3.40

COMPOSITED ASSAY OF SELECTED INTERVALS

WARNING!!!! NON-CONTIGUOUS SAMPLES!!!!!!

S.G. and length weighted composites:

number of samples	from (m)	to (m)	interval (m)	Pb+Zn (%)	Pb (%)	Zn (%)	Ag (g/t)	Au (g/t)	S.G.
3	41.4	47.6	6.0	14.17	5.01	9.16	51.0	0.34	3.44

Length weighted composites:

number of samples	from (m)	to (m)	interval (m)	Pb+Zn (%)	Pb (%)	Zn (%)	Ag (g/t)	Au (g/t)	S.G.
3	41.4	47.6	6.0	14.16	5.00	9.17	50.9	0.34	3.44

CURRAGH RESOURCES INC.
 VANGORDA PROJECT, FARO, YUKON

DRILLHOLE COMPOSITES SECTION: 12_0E POLYGON: 12E11

hole	from	to	interval	rock code	Pb+Zn	Pb(%)	Zn(%)	Ag(g/t)	Au(g/t)	S.G.
79V309	52.7	54.3	1.6	61	12.33	4.28	8.05	58.0	0.25	4.27
79V312	41.4	43.0	1.6	32	9.81	3.01	6.80	44.0	0.68	3.40

COMPOSITED ASSAY OF SELECTED INTERVALS-----

WARNING!!!! NON-CONTIGUOUS SAMPLES!!!!!!!

S.G. and length weighted composites:

number of samples	from (m)	to (m)	interval (m)	Pb+Zn (%)	Pb (%)	Zn (%)	Ag (g/t)	Au (g/t)	S.G.
2	41.4	54.3	3.2	11.21	3.72	7.50	51.8	0.44	3.83

Length weighted composites:

number of samples	from (m)	to (m)	interval (m)	Pb+Zn (%)	Pb (%)	Zn (%)	Ag (g/t)	Au (g/t)	S.G.
2	41.4	54.3	3.2	11.07	3.64	7.42	51.0	0.47	3.83

Rec

CURRAGH RESOURCES INC.
 VANGORDA PROJECT, FARGO, YUKON

DRILLHOLE COMPOSITES SECTION: 12_0E POLY60N: 12E12

hole	from	to	interval	rock code	Pb+Zn	Pb(%)	Zn(%)	Ag(g/t)	Au(g/t)	S.G.
79V309	58.2	59.7	1.5	61	13.24	6.04	7.20	81.0	2.14	4.50
79V309	59.7	61.3	1.6	61	11.92	5.60	6.32	63.0	2.35	4.36
79V309	61.3	63.4	2.1	61	6.89	3.42	3.47	43.0	1.82	4.35
79V309	63.4	64.2	0.8	70	8.88	4.47	4.41	66.0	0.45	3.73

COMPOSITED ASSAY OF SELECTED INTERVALS

S.G. and length weighted composites:

number of samples	from (m)	to (m)	interval (m)	Pb+Zn (%)	Pb (%)	Zn (%)	Ag (g/t)	Au (g/t)	S.G.
4	58.2	64.2	6.0	10.14	4.81	5.32	61.0	1.89	4.31

Length weighted composites:

number of samples	from (m)	to (m)	interval (m)	Pb+Zn (%)	Pb (%)	Zn (%)	Ag (g/t)	Au (g/t)	S.G.
4	58.2	64.2	6.0	10.08	4.80	5.29	60.9	1.86	4.31

CURRAGH RESOURCES INC.
VANGORDA PROJECT, FARO, YUKON

DRILLHOLE COMPOSITES SECTION: 12_0E POLYGON: 12E13

hole	from	to	interval	rock code	Pb+Zn	Pb(%)	Zn(%)	Ag(g/t)	Au(g/t)	S.G.
79V063R	28.7	30.2	1.5	61	11.77	7.09	4.68	88.0	0.62	4.84
79V063R	30.2	31.7	1.5	61	6.86	2.90	3.96	35.0	0.51	3.91
79V063R	31.7	33.5	1.8	61	13.00	4.28	8.72	43.0	0.14	4.11
79V063R	33.5	35.7	2.2	80	7.09	3.14	3.95	46.0	0.72	3.94
79V063R	35.7	37.2	1.5	80	10.17	5.21	4.96	64.0	1.58	4.01
79V063R	37.2	38.7	1.5	31	1.79	0.81	0.98	18.0	0.79	3.33
79V063R	38.7	40.2	1.5	31	7.62	3.70	3.92	56.0	0.75	3.58
79V063R	40.2	41.8	1.6	31	10.14	5.25	4.89	47.0	0.72	3.70

COMPOSITED ASSAY OF SELECTED INTERVALS-----

S.G. and length weighted composites:

number of samples	from (m)	to (m)	interval (m)	Pb+Zn (%)	Pb (%)	Zn (%)	Ag (g/t)	Au (g/t)	S.G.
8	28.7	41.8	13.1	8.82	4.15	4.67	50.8	0.71	3.93

Length weighted composites:

number of samples	from (m)	to (m)	interval (m)	Pb+Zn (%)	Pb (%)	Zn (%)	Ag (g/t)	Au (g/t)	S.G.
8	28.7	41.8	13.1	8.59	4.01	4.58	49.3	0.71	3.93

CURRAGH RESOURCES INC.
 VANGORDA PROJECT, FARD, YUKON

DRILLHOLE COMPOSITES SECTION: 12_0E POLYGON: 12E14

hole	from	to	interval	rock code	Pb+Zn	Pb(%)	Zn(%)	Ag(g/t)	Au(g/t)	S.G.
79V309	33.8	35.4	1.6	61	10.09	5.06	5.03	43.0	0.39	4.23

COMPOSITED ASSAY OF SELECTED INTERVALS

S.G. and length weighted composites:

number of samples	from (m)	to (m)	interval (m)	Pb+Zn (%)	Pb (%)	Zn (%)	Ag (g/t)	Au (g/t)	S.G.
1	33.8	35.4	1.6	10.09	5.06	5.03	43.0	0.39	4.23

Length weighted composites:

number of samples	from (m)	to (m)	interval (m)	Pb+Zn (%)	Pb (%)	Zn (%)	Ag (g/t)	Au (g/t)	S.G.
1	33.8	35.4	1.6	10.09	5.06	5.03	43.0	0.39	4.23

CURRAGH RESOURCES INC.
 VANGORDA PROJECT, FARO, YUKON

DRILLHOLE COMPOSITES SECTION: 13_0E POLYGON: 13E1

hole	from	to	interval	rock code	Pb+Zn	Pb(%)	Zn(%)	Ag(g/t)	Au(g/t)	S.G.
88V-05	29.6	30.6	1.0	61	16.30	5.70	10.60	89.0	3.09	3.40
88V-05	30.6	31.7	1.1	61	9.79	5.80	3.99	91.0	1.58	4.90
88V-05	31.7	32.8	1.1	61	10.84	5.03	5.81	75.0	0.69	3.80
88V-05	32.8	34.0	1.2	61	15.34	8.10	7.24	108.0	1.03	4.20
88V-05	34.0	35.1	1.1	61	19.14	10.40	8.74	136.0	0.82	4.40
88V-05	35.1	35.9	0.8	61	17.96	10.20	7.76	108.0	0.62	4.10
88V-05	35.9	36.7	0.8	61	4.61	2.13	2.48	55.0	0.34	3.90
88V-05	36.7	37.5	0.8	61	7.93	4.26	3.67	57.0	1.03	3.60
88V-05	37.5	38.7	1.2	61	17.79	8.30	9.49	128.0	1.10	4.10
88V-05	38.7	39.5	0.8	61	15.16	6.03	9.13	92.0	1.10	3.80
88V-05	39.5	40.9	1.4	61	19.62	12.30	7.32	124.0	1.95	4.50
88V-05	40.9	42.4	1.5	61	16.42	8.18	8.24	81.0	1.51	4.50
88V-05	42.4	43.6	1.2	61	14.73	6.32	8.41	104.0	1.61	4.00
88V-05	43.6	45.0	1.4	61	12.40	5.94	6.46	98.0	1.58	4.40
88V-05	45.0	46.0	1.0	41	6.45	3.30	3.15	41.0	1.58	3.90

SECTION: 13_0E POLYGON: 13E1

COMPOSITED ASSAY OF SELECTED INTERVALS-----

S.G. and length weighted composites:

number of samples	from (m)	to (m)	interval (m)	Pb+Zn (%)	Pb (%)	Zn (%)	Ag (g/t)	Au (g/t)	S.G.
15	29.6	46	16.4	14.12	7.16	6.96	95.6	1.35	4.15

Length weighted composites:

number of samples	from (m)	to (m)	interval (m)	Pb+Zn (%)	Pb (%)	Zn (%)	Ag (g/t)	Au (g/t)	S.G.
15	29.6	46	16.4	14.02	7.04	6.98	94.6	1.36	4.15

CURRAGH RESOURCES INC.
 VANGORDA PROJECT, FARO, YUKON

DRILLHOLE COMPOSITES SECTION: 13_0E POLYGON: 13E2

hole	from	to	interval	rock code	Pb+Zn	Pb(%)	Zn(%)	Ag(g/t)	Au(g/t)	S.G.
88V-05	52.5	53.8	1.3	61	13.25	5.23	8.02	73.0	0.82	3.70
88V-05	53.8	55.3	1.5	61	9.14	4.35	4.79	63.0	1.51	3.90
88V-05	55.3	56.5	1.2	61	11.51	5.13	6.38	86.0	1.23	4.10

SECTION: 13_0E POLYGON: 13E2

COMPOSITED ASSAY OF SELECTED INTERVALS-----

S.G. and length weighted composites:

number of samples	from (m)	to (m)	interval (m)	Pb+Zn (%)	Pb (%)	Zn (%)	Ag (g/t)	Au (g/t)	S.G.
3	52.5	56.5	4	11.16	4.87	6.29	73.4	1.21	3.90

Length weighted composites:

number of samples	from (m)	to (m)	interval (m)	Pb+Zn (%)	Pb (%)	Zn (%)	Ag (g/t)	Au (g/t)	S.G.
3	52.5	56.5	4	11.19	4.87	6.32	73.2	1.20	3.90

CURRAGH RESOURCES INC.
 VANGORDA PROJECT, FARD, YUKON

DRILLHOLE COMPOSITES SECTION: 14_OE POLYGON: 14E1

hole	from	to	interval	rock code	Pb+Zn	Pb(%)	Zn(%)	Ag(g/t)	Au(g/t)	S.G.
88V-50	40.5	41.7	1.2	62	9.80	3.28	6.52	57.0	0.34	3.20
88V-50	41.7	42.4	0.7	62	6.16	3.77	2.39	54.0	0.34	4.20

SECTION: 14_OE POLYGON: 14E1

COMPOSITED ASSAY OF SELECTED INTERVALS-----

S.G. and length weighted composites:

number of samples	from (m)	to (m)	interval (m)	Pb+Zn (%)	Pb (%)	Zn (%)	Ag (g/t)	Au (g/t)	S.G.
2	40.5	42.4	1.9	8.22	3.49	4.73	55.7	0.34	3.57

Length weighted composites:

number of samples	from (m)	to (m)	interval (m)	Pb+Zn (%)	Pb (%)	Zn (%)	Ag (g/t)	Au (g/t)	S.G.
2	40.5	42.4	1.9	8.46	3.46	5.00	55.9	0.34	3.57

CURRAGH RESOURCES INC.
 VANGORDA PROJECT, FARD, YUKON

DRILLHOLE COMPOSITES SECTION: 14_0E POLYGON: 14E2

hole	from	to	interval	rock code	Pb+Zn	Pb(%)	Zn(%)	Ag(g/t)	Au(g/t)	S.G.
P54V040	16.7	18.2	1.5	62	17.28	9.61	7.67	-1.0	-1.00	4.21
P54V040	18.2	19.5	1.3	62	21.34	9.94	11.40	-1.0	-1.00	4.21

COMPOSITED ASSAY OF SELECTED INTERVALS-----

S.G. and length weighted composites:

number of samples	from (m)	to (m)	interval (m)	Pb+Zn (%)	Pb (%)	Zn (%)	Ag (g/t)	Au (g/t)	S.G.
2	16.7	19.5	2.8	19.17	9.76	9.40	-1.0	-1.00	4.21

Length weighted composites:

number of samples	from (m)	to (m)	interval (m)	Pb+Zn (%)	Pb (%)	Zn (%)	Ag (g/t)	Au (g/t)	S.G.
2	16.7	19.5	2.8	19.17	9.76	9.40	-1.0	-1.00	4.21

CURRAGH RESOURCES INC.
 VANGORDA PROJECT, FARD, YUKON

DRILLHOLE COMPOSITES SECTION: 14_0E POLYGON: 14E3

hole	from	to	interval	rock code	Pb+Zn	Pb(%)	Zn(%)	Ag(g/t)	Au(g/t)	S.G.
BBV-09	22.9	24.0	1.1	62	17.53	8.26	9.27	138.0	0.99	4.30
BBV-09	24.0	25.1	1.1	62	10.15	4.78	5.37	63.0	1.20	4.40
BBV-09	25.1	26.5	1.4	62	9.13	5.05	4.08	75.0	0.55	4.10

SECTION: 14_0E POLYGON: 14E3

COMPOSITED ASSAY OF SELECTED INTERVALS-----

S.G. and length weighted composites:

number of samples	from (m)	to (m)	interval (m)	Pb+Zn (%)	Pb (%)	Zn (%)	Ag (g/t)	Au (g/t)	S.G.
3	22.9	26.5	3.6	12.05	5.96	6.09	90.7	0.89	4.25

Length weighted composites:

number of samples	from (m)	to (m)	interval (m)	Pb+Zn (%)	Pb (%)	Zn (%)	Ag (g/t)	Au (g/t)	S.G.
3	22.9	26.5	3.6	12.01	5.95	6.06	90.6	0.88	4.25

CURRAGH RESOURCES INC.
 VANGORDA PROJECT, FARO, YUKON

DRILLHOLE COMPOSITES SECTION: 14_0E POLY6DN: 14E4

hole	from	to	interval	rock code	Pb+Zn	Pb(%)	Zn(%)	Ag(g/t)	Au(g/t)	S.G.
P55V098	30.3	31.0	0.7	62	5.92	3.06	2.86	-1.0	-1.00	4.21
P55V098	31.0	32.3	1.3	62	7.75	3.83	3.92	-1.0	-1.00	4.21

COMPOSITED ASSAY OF SELECTED INTERVALS

S.G. and length weighted composites:

number of samples	from (m)	to (m)	interval (m)	Pb+Zn (%)	Pb (%)	Zn (%)	Ag (g/t)	Au (g/t)	S.G.
2	30.3	32.3	2.0	7.11	3.56	3.55	-1.0	-1.00	4.21

Length weighted composites:

number of samples	from (m)	to (m)	interval (m)	Pb+Zn (%)	Pb (%)	Zn (%)	Ag (g/t)	Au (g/t)	S.G.
2	30.3	32.3	2.0	7.11	3.56	3.55	-1.0	-1.00	4.21

CURRAGH RESOURCES INC.
 VANGORDA PROJECT, FARO, YUKON

DRILLHOLE COMPOSITES SECTION: 14_0E POLYGON: 14E5

hole	from	to	interval	rock code	Pb+Zn	Pb(%)	Zn(%)	Ag(g/t)	Au(g/t)	S.G.
P55V098	36.8	38.4	1.6	22	11.98	4.15	7.83	-1.0	-1.00	2.97
P55V098	38.4	39.9	1.5	22	13.03	3.83	9.20	-1.0	-1.00	2.97
P55V098	39.9	40.5	0.6	22	10.46	3.06	7.40	-1.0	-1.00	2.97

COMPOSITED ASSAY OF SELECTED INTERVALS

S.G. and length weighted composites:

number of samples	from (m)	to (m)	interval (m)	Pb+Zn (%)	Pb (%)	Zn (%)	Ag (g/t)	Au (g/t)	S.G.
3	36.8	40.5	3.7	12.16	3.84	8.32	-1.0	-1.00	2.97

Length weighted composites:

number of samples	from (m)	to (m)	interval (m)	Pb+Zn (%)	Pb (%)	Zn (%)	Ag (g/t)	Au (g/t)	S.G.
3	36.8	40.5	3.7	12.16	3.84	8.32	-1.0	-1.00	2.97

CURRAGH RESOURCES INC.
 VANGORDA PROJECT, FARO, YUKON

DRILLHOLE COMPOSITES SECTION: 14_0E POLYGON: 14E6

hole	from	to	interval	rock code	Pb+Zn	Pb(%)	Zn(%)	Ag(g/t)	Au(g/t)	S.G.
P55V098	44.6	46.0	1.4	61	10.14	3.06	7.08	-1.0	-1.00	4.21

COMPOSITED ASSAY OF SELECTED INTERVALS

S.G. and length weighted composites:

number of samples	from (m)	to (m)	interval (m)	Pb+Zn (%)	Pb (%)	Zn (%)	Ag (g/t)	Au (g/t)	S.G.
1	44.6	46.0	1.4	10.14	3.06	7.08	-1.0	-1.00	4.21

Length weighted composites:

number of samples	from (m)	to (m)	interval (m)	Pb+Zn (%)	Pb (%)	Zn (%)	Ag (g/t)	Au (g/t)	S.G.
1	44.6	46.0	1.4	10.14	3.06	7.08	-1.0	-1.00	4.21

CURRAGH RESOURCES INC.
 VANGORDA PROJECT, FARO, YUKON

DRILLHOLE COMPOSITES SECTION: 14_0E POLYGON: 14E7

hole	from	to	interval	rock code	Pb+Zn	Pb(%)	Zn(%)	Ag(g/t)	Au(g/t)	S.G.
88Y-08	31.5	34.2	2.7	50	6.75	2.07	4.68	24.0	0.14	3.10

SECTION: 14_0E POLYGON: 14E7

COMPOSITED ASSAY OF SELECTED INTERVALS

S.G. and length weighted composites:

number of samples	from (m)	to (m)	interval (m)	Pb+Zn (%)	Pb (%)	Zn (%)	Ag (g/t)	Au (g/t)	S.G.
1	31.5	34.2	2.7	6.75	2.07	4.68	24.0	0.14	3.10

Length weighted composites:

number of samples	from (m)	to (m)	interval (m)	Pb+Zn (%)	Pb (%)	Zn (%)	Ag (g/t)	Au (g/t)	S.G.
1	31.5	34.2	2.7	6.75	2.07	4.68	24.0	0.14	3.10

CURRAGH RESOURCES INC.
VANGORDA PROJECT, FARO, YUKON

DRILLHOLE COMPOSITES SECTION: 14_0E POLYGON: 14EB

hole	from	to	interval	rock code	Pb+Zn	Pb(%)	Zn(%)	Ag(g/t)	Au(g/t)	S.G.
88V-08	36.3	37.5	1.2	61	13.21	5.26	7.95	62.0	0.69	4.20
88V-08	37.5	38.5	1.0	61	6.64	2.78	3.86	38.0	0.27	3.60
88V-08	38.5	39.4	0.9	61	10.74	4.91	5.83	55.0	0.48	4.20
88V-08	39.4	40.6	1.2	61	12.97	5.76	7.21	72.0	0.96	4.10
88V-08	40.6	41.3	0.7	61	8.71	2.86	5.85	36.0	0.27	3.30
88V-08	41.3	42.3	1.0	61	0.29	0.01	0.28	5.0	0.07	2.90
88V-08	42.3	43.9	1.6	61	16.32	7.77	8.55	100.0	1.23	4.30
88V-08	43.9	45.2	1.3	61	16.75	8.41	8.34	77.0	0.41	4.50
88V-08	45.2	46.5	1.3	61	16.09	8.14	7.95	85.0	1.37	4.40
88V-08	46.5	47.9	1.4	61	16.99	8.43	8.56	119.0	1.58	4.50
88V-08	47.9	48.7	0.8	61	10.37	5.95	4.42	68.0	1.03	4.50

SECTION: 14_0E POLYGON: 14EB

COMPOSITED ASSAY OF SELECTED INTERVALS

S.G. and length weighted composites:

number of samples	from (m)	to (m)	interval (m)	Pb+Zn (%)	Pb (%)	Zn (%)	Ag (g/t)	Au (g/t)	S.G.
11	36.3	48.7	12.4	13.02	6.17	6.85	73.2	0.87	4.10

Length weighted composites:

number of samples	from (m)	to (m)	interval (m)	Pb+Zn (%)	Pb (%)	Zn (%)	Ag (g/t)	Au (g/t)	S.G.
11	36.3	48.7	12.4	12.50	5.88	6.62	70.2	0.83	4.10

CURRAGH RESOURCES INC.
 VANGORDA PROJECT, FAHO, YUKON

DRILLHOLE COMPOSITES SECTION: 14_0E POLYGON: 14E10

hole	from	to	interval	rock code	Pb+Zn	Pb(%)	Zn(%)	Ag(g/t)	Au(g/t)	S.G.
88V-08	52.2	53.9	1.7	61	6.75	2.73	4.02	56.0	3.46	3.70

SECTION: 14_0E POLYGON: 14E10

COMPOSITED ASSAY OF SELECTED INTERVALS

S.G. and length weighted composites:

number of samples	from (m)	to (m)	interval (m)	Pb+Zn (%)	Pb (%)	Zn (%)	Ag (g/t)	Au (g/t)	S.G.
1	52.2	53.9	1.7	6.75	2.73	4.02	56.0	3.46	3.70

Length weighted composites:

number of samples	from (m)	to (m)	interval (m)	Pb+Zn (%)	Pb (%)	Zn (%)	Ag (g/t)	Au (g/t)	S.G.
1	52.2	53.9	1.7	6.75	2.73	4.02	56.0	3.46	3.70

CURRAGH RESOURCES INC.
 VANGOROA PROJECT, FARO, YUKON

DRILLHOLE COMPOSITES SECTION: 14_0E POLYGON: 14E11

hole	from	to	interval	rock code	Pb+Zn	Pb(%)	Zn(%)	Ag(g/t)	Au(g/t)	S.G.
P54V052	32.0	33.5	1.5	61	12.95	6.42	6.53	-1.0	-1.00	4.21
P54V052	33.5	35.0	1.5	61	13.08	4.83	8.25	-1.0	-1.00	4.21
P54V052	35.0	36.5	1.5	61	14.19	4.04	10.15	-1.0	-1.00	4.21
P54V052	36.5	38.1	1.6	61	9.45	2.71	6.74	-1.0	-1.00	4.21

COMPOSITED ASSAY OF SELECTED INTERVALS-----

S.G. and length weighted composites:

number of samples	from (m)	to (m)	interval (m)	Pb+Zn (%)	Pb (%)	Zn (%)	Ag (g/t)	Au (g/t)	S.G.
4	32.0	38.1	6.1	12.37	4.47	7.90	-1.0	-1.00	4.21

Length weighted composites:

number of samples	from (m)	to (m)	interval (m)	Pb+Zn (%)	Pb (%)	Zn (%)	Ag (g/t)	Au (g/t)	S.G.
4	32.0	38.1	6.1	12.37	4.47	7.90	-1.0	-1.00	4.21

CURRAGH RESOURCES INC.
 VANGORDA PROJECT, FARD, YUKON

DRILLHOLE COMPOSITES SECTION: 14_0E POLYGON: 14E12

hole	from	to	interval	rock code	Pb+Zn	Pb(%)	Zn(%)	Ag(g/t)	Au(g/t)	S.G.
P54V052	44.1	45.7	1.6	61	7.24	3.02	4.22	-1.0	-1.00	4.21
P54V052	45.7	47.2	1.5	61	7.28	2.45	4.83	-1.0	-1.00	4.21

COMPOSITED ASSAY OF SELECTED INTERVALS

S.G. and length weighted composites:

number of samples	from (m)	to (m)	interval (m)	Pb+Zn (%)	Pb (%)	Zn (%)	Ag (g/t)	Au (g/t)	S.G.
2	44.1	47.2	3.1	7.26	2.74	4.52	-1.0	-1.00	4.21

Length weighted composites:

number of samples	from (m)	to (m)	interval (m)	Pb+Zn (%)	Pb (%)	Zn (%)	Ag (g/t)	Au (g/t)	S.G.
2	44.1	47.2	3.1	7.26	2.74	4.52	-1.0	-1.00	4.21

CURRAGH RESOURCES INC.
VANGORDA PROJECT, FARO, YUKON

DRILLHOLE COMPOSITES SECTION: 14_0E POLYGON: 14E13

hole	from	to	interval	rock code	Pb+Zn	Pb(%)	Zn(%)	Ag(g/t)	Au(g/t)	S.G.
87V-02	22.9	25.0	2.1	61	13.67	6.14	7.53	78.0	0.55	4.50
87V-02	25.0	26.5	1.5	61	14.35	8.92	5.43	107.0	0.75	4.20
87V-02	26.5	28.0	1.5	61	11.23	6.69	4.54	96.0	0.65	4.10
87V-02	28.0	30.2	2.2	61	7.22	4.27	2.95	50.0	0.31	3.50
87V-02	30.2	31.1	0.9	61	15.70	9.40	6.30	153.0	0.82	4.40
87V-02	31.1	32.1	1.0	61	8.15	5.67	2.48	63.0	0.82	4.20
87V-02	32.1	32.6	0.5	61	10.67	5.29	5.38	46.0	0.55	4.10
87V-02	32.6	33.0	0.4	130	5.68	1.59	4.09	64.0	0.41	3.20
87V-02	33.0	33.8	0.8	61	10.97	4.89	6.08	47.0	0.34	4.00
87V-02	33.8	34.7	0.9	61	8.08	3.07	5.01	30.0	0.24	4.40
87V-02	34.7	36.0	1.3	61	11.41	3.76	7.65	38.0	0.31	4.50
87V-02	36.0	36.6	0.6	61	0.62	0.31	0.31	11.0	0.99	4.70
87V-02	36.6	37.4	0.8	61	4.76	1.78	2.98	23.0	0.62	4.10
87V-02	37.4	38.5	1.1	61	16.67	7.72	8.95	64.0	0.17	4.10

SECTION: 14_0E POLYGON: 14E13

COMPOSITED ASSAY OF SELECTED INTERVALS-----

S.G. and length weighted composites:

number of samples	from (m)	to (m)	interval (m)	Pb+Zn (%)	Pb (%)	Zn (%)	Ag (g/t)	Au (g/t)	S.G.
14	22.9	38.5	15.6	10.76	5.46	5.30	66.8	0.53	4.15

Length weighted composites:

number of samples	from (m)	to (m)	interval (m)	Pb+Zn (%)	Pb (%)	Zn (%)	Ag (g/t)	Au (g/t)	S.G.
14	22.9	38.5	15.6	10.66	5.43	5.22	66.5	0.52	4.15

CURRAGH RESOURCES INC.
 VANGORDA PROJECT, FARO, YUKON

DRILLHOLE COMPOSITES SECTION: 14_0E POLYGON: 14E14

hole	from	to	interval	rock code	Pb+Zn	Pb(%)	Zn(%)	Ag(g/t)	Au(g/t)	S.G.
P55V097	28.6	30.1	1.5	61	9.21	3.61	5.60	-1.0	-1.00	4.21
P55V097	30.1	31.6	1.5	61	13.15	7.87	5.28	-1.0	-1.00	4.21
P55V097	31.6	33.2	1.6	61	11.06	5.36	5.70	-1.0	-1.00	4.21
P55V097	33.2	34.7	1.5	61	7.71	3.06	4.65	-1.0	-1.00	4.21
P55V097	34.7	36.2	1.5	61	3.48	1.26	2.22	-1.0	-1.00	4.21
P55V097	36.2	37.7	1.5	61	4.59	1.10	3.49	-1.0	-1.00	4.21
P55V097	37.7	39.3	1.6	61	11.89	7.66	4.23	-1.0	-1.00	4.21

COMPOSITED ASSAY OF SELECTED INTERVALS

S.G. and length weighted composites:

number of samples	from (m)	to (m)	interval (m)	Pb+Zn (%)	Pb (%)	Zn (%)	Ag (g/t)	Au (g/t)	S.G.
7	28.6	39.3	10.7	8.78	4.32	4.46	-1.0	-1.00	4.21

Length weighted composites:

number of samples	from (m)	to (m)	interval (m)	Pb+Zn (%)	Pb (%)	Zn (%)	Ag (g/t)	Au (g/t)	S.G.
7	28.6	39.3	10.7	8.78	4.32	4.46	-1.0	-1.00	4.21

CURRAGH RESOURCES INC.
 VANGORDA PROJECT, FARO, YUKON

DRILLHOLE COMPOSITES SECTION: 14_0E POLYGON: 14E15

hole	from	to	interval	rock code	Pb+Zn	Pb(%)	Zn(%)	Ag(g/t)	Au(g/t)	S.G.
P55V097	43.8	45.4	1.6	41	5.01	4.16	0.85	-1.0	-1.00	3.77
P55V097	45.4	46.9	1.5	41	6.68	5.15	1.53	-1.0	-1.00	3.77

COMPOSITED ASSAY OF SELECTED INTERVALS-----

S.G. and length weighted composites:

number of samples	from (m)	to (m)	interval (m)	Pb+Zn (%)	Pb (%)	Zn (%)	Ag (g/t)	Au (g/t)	S.G.
2	43.8	46.9	3.1	5.82	4.64	1.18	-1.0	-1.00	3.77

Length weighted composites:

number of samples	from (m)	to (m)	interval (m)	Pb+Zn (%)	Pb (%)	Zn (%)	Ag (g/t)	Au (g/t)	S.G.
2	43.8	46.9	3.1	5.82	4.64	1.18	-1.0	-1.00	3.77

CURRAGH RESOURCES INC.
 VANGORDA PROJECT, FARO, YUKON

DRILLHOLE COMPOSITES SECTION: 14_0E POLYGON: 14E16

hole	from	to	interval	rock code	Pb+Zn	Pb(%)	Zn(%)	Ag(g/t)	Au(g/t)	S.G.
87V-01	21.9	23.5	1.6	61	14.15	5.87	8.28	101.0	0.55	4.50
87V-01	23.5	25.8	2.3	61	9.90	3.18	6.72	42.0	0.82	4.30
87V-01	25.8	26.6	0.8	61	12.61	5.36	7.25	113.0	0.24	4.70
87V-01	26.6	27.0	0.4	130	4.46	0.54	3.92	10.0	0.07	3.10
87V-01	27.0	28.3	1.3	61	5.97	2.41	3.56	40.0	0.69	4.20
87V-01	28.3	29.4	1.1	61	6.16	2.79	3.37	34.0	0.79	4.00
87V-01	29.4	30.5	1.1	61	14.33	6.89	7.44	99.0	0.65	4.60
87V-01	30.5	31.0	0.5	130	2.10	0.45	1.65	10.0	0.24	3.00
87V-01	31.0	31.9	0.9	80	11.26	5.94	5.32	83.0	0.55	4.30
87V-01	31.9	33.2	1.3	61	14.70	7.07	7.63	93.0	0.51	4.60
87V-01	33.2	34.7	1.5	61	14.95	7.03	7.92	85.0	0.69	4.60
87V-01	34.7	35.9	1.2	80	21.20	10.30	10.90	114.0	0.93	4.00
87V-01	35.9	37.0	1.1	80	14.76	6.84	7.92	77.0	0.96	3.70

SECTION: 14_0E POLYGON: 14E16

COMPOSITED ASSAY OF SELECTED INTERVALS

S.G. and length weighted composites:

number of samples	from (m)	to (m)	interval (m)	Pb+Zn (%)	Pb (%)	Zn (%)	Ag (g/t)	Au (g/t)	S.G.
13	21.9	37	15.1	12.23	5.40	6.83	74.7	0.66	4.25

Length weighted composites:

number of samples	from (m)	to (m)	interval (m)	Pb+Zn (%)	Pb (%)	Zn (%)	Ag (g/t)	Au (g/t)	S.G.
13	21.9	37	15.1	12.05	5.31	6.74	72.9	0.66	4.25

CURRAGH RESOURCES INC.
 VANGORDA PROJECT, FARO, YUKON

DRILLHOLE COMPOSITES SECTION: 14_0E POLYGON: 14E17

hole	from	to	interval	rock code	Pb+Zn	Pb(%)	Zn(%)	Ag(g/t)	Au(g/t)	S.G.
P54V056	26.8	28.1	1.3	61	17.67	9.45	8.22	-1.0	-1.00	4.21
P54V056	28.1	29.6	1.5	61	9.59	2.48	7.11	-1.0	-1.00	4.21
P54V056	29.6	31.1	1.5	61	6.24	1.66	4.58	-1.0	-1.00	4.21

COMPOSITED ASSAY OF SELECTED INTERVALS

S.G. and length weighted composites:

number of samples	from (m)	to (m)	interval (m)	Pb+Zn (%)	Pb (%)	Zn (%)	Ag (g/t)	Au (g/t)	S.G.
3	26.8	31.1	4.3	10.86	4.30	6.56	-1.0	-1.00	4.21

Length weighted composites:

number of samples	from (m)	to (m)	interval (m)	Pb+Zn (%)	Pb (%)	Zn (%)	Ag (g/t)	Au (g/t)	S.G.
3	26.8	31.1	4.3	10.86	4.30	6.56	-1.0	-1.00	4.21

CURRAGH RESOURCES INC.
 VANGORDA PROJECT, FARO, YUKON

DRILLHOLE COMPOSITES SECTION: 14_0E POLYGON: 14E18

hole	from	to	interval	rock code	Pb+Zn	Pb(%)	Zn(%)	Ag(g/t)	Au(g/t)	S.G.
88V-08	29.9	31.5	1.6	22	8.44	2.82	5.62	42.0	0.65	2.80

SECTION: 14_0E POLYGON: 14E18

COMPOSITED ASSAY OF SELECTED INTERVALS-----

S.G. and length weighted composites:

number of samples	from (m)	to (m)	interval (m)	Pb+Zn (%)	Pb (%)	Zn (%)	Ag (g/t)	Au (g/t)	S.G.
1	29.9	31.5	1.6	8.44	2.82	5.62	42.0	0.65	2.80

Length weighted composites:

number of samples	from (m)	to (m)	interval (m)	Pb+Zn (%)	Pb (%)	Zn (%)	Ag (g/t)	Au (g/t)	S.G.
1	29.9	31.5	1.6	8.44	2.82	5.62	42.0	0.65	2.80

CURRAGH RESOURCES INC.
 VANGORDA PROJECT, FARD, YUKON

DRILLHOLE COMPOSITES SECTION: 15_0E POLYGON: 15E1

hole	from	to	interval	rock code	Pb+Zn	Pb(%)	Zn(%)	Ag(g/t)	Au(g/t)	S.G.
88V-10	25.2	26.4	1.2	62	10.20	5.84	4.36	81.0	1.17	4.20
88V-10	26.4	27.8	1.4	62	2.09	0.35	1.74	8.0	0.14	2.80
88V-10	27.8	28.1	0.3	62	7.45	4.90	2.55	64.0	0.62	4.00

SECTION: 15_0E POLYGON: 15E1

COMPOSITED ASSAY OF SELECTED INTERVALS-----

S.G. and length weighted composites:

number of samples	from (m)	to (m)	interval (m)	Pb+Zn (%)	Pb (%)	Zn (%)	Ag (g/t)	Au (g/t)	S.G.
3	25.2	28.1	2.9	6.75	3.61	3.14	50.8	0.71	3.50

Length weighted composites:

number of samples	from (m)	to (m)	interval (m)	Pb+Zn (%)	Pb (%)	Zn (%)	Ag (g/t)	Au (g/t)	S.G.
3	25.2	28.1	2.9	6.00	3.09	2.91	44.0	0.62	3.50

CURRAGH RESOURCES INC.
 VANGORDA PROJECT, FARO, YUKON

DRILLHOLE COMPOSITES SECTION: 15_0E POLYGON: 15E2

hole	from	to	interval	rock code	Pb+Zn	Pb(%)	Zn(%)	Ag(g/t)	Au(g/t)	S.G.
BBV-10	40.2	40.8	0.6	61	11.44	3.71	7.73	89.0	0.62	3.00
BBV-10	40.8	42.1	1.3	61	10.92	3.76	7.16	72.0	0.21	3.90
BBV-10	42.1	43.6	1.5	41	0.56	0.13	0.43	4.0	0.14	2.90
BBV-10	43.6	44.6	1.0	41	10.19	3.75	6.44	43.0	0.14	3.90

SECTION: 15_0E POLYGON: 15E2

COMPOSITED ASSAY OF SELECTED INTERVALS

S.G. and length weighted composites:

number of samples	from (m)	to (m)	interval (m)	Pb+Zn (%)	Pb (%)	Zn (%)	Ag (g/t)	Au (g/t)	S.G.
4	40.2	44.6	4.4	7.81	2.71	5.11	47.0	0.22	3.44

Length weighted composites:

number of samples	from (m)	to (m)	interval (m)	Pb+Zn (%)	Pb (%)	Zn (%)	Ag (g/t)	Au (g/t)	S.G.
4	40.2	44.6	4.4	7.29	2.51	4.78	44.5	0.23	3.44

CURRAGH RESOURCES INC.
 VANGORDA PROJECT, FARO, YUKON

DRILLHOLE COMPOSITES SECTION: 15_0E POLYGON: 15E3

hole	from	to	interval	rock code	Pb+Zn	Pb(%)	Zn(%)	Ag(g/t)	Au(g/t)	S.G.
88V-16	21.9	24.1	2.2	22	7.88	4.63	3.25	60.0	0.51	2.50

SECTION: 15_0E POLYGON: 15E3

COMPOSITED ASSAY OF SELECTED INTERVALS

S.G. and length weighted composites:

number of samples	from (m)	to (m)	interval (m)	Pb+Zn (%)	Pb (%)	Zn (%)	Ag (g/t)	Au (g/t)	S.G.
1	21.9	24.1	2.2	7.88	4.63	3.25	60.0	0.51	2.50

Length weighted composites:

number of samples	from (m)	to (m)	interval (m)	Pb+Zn (%)	Pb (%)	Zn (%)	Ag (g/t)	Au (g/t)	S.G.
1	21.9	24.1	2.2	7.88	4.63	3.25	60.0	0.51	2.50

CURRAGH RESOURCES INC.
 VANGORDA PROJECT, FARD, YUKON

DRILLHOLE COMPOSITES SECTION: 15_0E POLY60N: 15E4

hole	from	to	interval	rock code	Pb+Zn	Pb(%)	Zn(%)	Ag(g/t)	Au(g/t)	S.G.
88V-16	27.4	28.7	1.3	61	12.90	6.47	6.43	107.0	1.13	4.60
88V-16	28.7	29.7	1.0	61	10.59	4.44	6.15	91.0	1.17	4.30
88V-16	29.7	30.8	1.1	61	11.92	4.33	7.59	70.0	0.99	4.30

SECTION: 15_0E POLY60N: 15E4

COMPOSITED ASSAY OF SELECTED INTERVALS

S.G. and length weighted composites:

number of samples	from (m)	to (m)	interval (m)	Pb+Zn (%)	Pb (%)	Zn (%)	Ag (g/t)	Au (g/t)	S.G.
3	27.4	30.8	3.4	11.93	5.21	6.72	90.8	1.10	4.41

Length weighted composites:

number of samples	from (m)	to (m)	interval (m)	Pb+Zn (%)	Pb (%)	Zn (%)	Ag (g/t)	Au (g/t)	S.G.
3	27.4	30.8	3.4	11.90	5.18	6.72	90.3	1.10	4.41

CURRAGH RESOURCES INC.
VANGORDA PROJECT, FARO, YUKON

DRILLHOLE COMPOSITES SECTION: 15_0E POLYGON: 15E5

hole	from	to	interval	rock code	Pb+Zn	Pb(%)	Zn(%)	Ag(g/t)	Au(g/t)	S.G.
88V-13	23.5	25.0	1.5	61	6.13	3.16	2.97	38.0	0.24	4.10
88V-13	25.0	26.8	1.8	61	7.94	3.56	4.38	46.0	0.21	4.20
88V-13	26.8	27.7	0.9	61	12.83	4.56	8.27	40.0	0.10	4.20
88V-13	27.7	28.5	0.8	61	12.07	5.20	6.87	40.0	0.17	4.10
88V-13	28.5	29.6	1.1	80	11.81	6.62	5.19	59.0	0.45	4.40
88V-13	29.6	31.1	1.5	80	11.41	5.94	5.47	60.0	0.89	4.00
88V-13	31.1	32.4	1.3	80	20.49	8.69	11.80	71.0	0.55	4.30
88V-13	32.4	33.7	1.3	80	14.51	7.48	7.03	86.0	1.58	3.80

SECTION: 15_0E POLYGON: 15E5

COMPOSITED ASSAY OF SELECTED INTERVALS-----

S.G. and length weighted composites:

number of samples	from (m)	to (m)	interval (m)	Pb+Zn (%)	Pb (%)	Zn (%)	Ag (g/t)	Au (g/t)	S.G.
8	23.5	33.7	10.2	11.81	5.55	6.26	55.3	0.53	4.13

Length weighted composites:

number of samples	from (m)	to (m)	interval (m)	Pb+Zn (%)	Pb (%)	Zn (%)	Ag (g/t)	Au (g/t)	S.G.
8	23.5	33.7	10.2	11.79	5.55	6.24	55.6	0.55	4.13

CURRAGH RESOURCES INC.
 VANGORDA PROJECT, FARD, YUKON

DRILLHOLE COMPOSITES SECTION: 16_0E POLYGON: 16E1

hole	from	to	interval	rock code	Pb+Zn	Pb(%)	Zn(%)	Ag(g/t)	Au(g/t)	S.G.
BBV-11	22.9	23.8	0.9	120	11.55	4.57	6.98	64.0	0.75	4.00

SECTION: 16_0E POLYGON: 16E1

COMPOSITED ASSAY OF SELECTED INTERVALS

S.G. and length weighted composites:

number of samples	from (m)	to (m)	interval (m)	Pb+Zn (%)	Pb (%)	Zn (%)	Ag (g/t)	Au (g/t)	S.G.
1	22.9	23.8	0.9	11.55	4.57	6.98	64.0	0.75	4.00

Length weighted composites:

number of samples	from (m)	to (m)	interval (m)	Pb+Zn (%)	Pb (%)	Zn (%)	Ag (g/t)	Au (g/t)	S.G.
1	22.9	23.8	0.9	11.55	4.57	6.98	64.0	0.75	4.00

CURRAGH RESOURCES INC.
 VANGORDA PROJECT, FARD, YUKON

DRILLHOLE COMPOSITES SECTION: 16_0E POLYGON: 16E2

hole	from	to	interval	rock code	Pb+Zn	Pb(%)	Zn(%)	Ag(g/t)	Au(g/t)	S.G.
88V-11	27.4	28.9	1.5	120	7.78	2.72	5.06	32.0	0.21	2.80

SECTION: 16_0E POLYGON: 16E2

COMPOSITED ASSAY OF SELECTED INTERVALS

S.G. and length weighted composites:

number of samples	from (m)	to (m)	interval (m)	Pb+Zn (%)	Pb (%)	Zn (%)	Ag (g/t)	Au (g/t)	S.G.
1	27.4	28.9	1.5	7.78	2.72	5.06	32.0	0.21	2.80

Length weighted composites:

number of samples	from (m)	to (m)	interval (m)	Pb+Zn (%)	Pb (%)	Zn (%)	Ag (g/t)	Au (g/t)	S.G.
1	27.4	28.9	1.5	7.78	2.72	5.06	32.0	0.21	2.80

CURRAGH RESOURCES INC.
VANGORDA PROJECT, FARO, YUKON

DRILLHOLE COMPOSITES SECTION: 16_0E POLYGON: 16E3

hole	from	to	interval	rock code	Pb+Zn	Pb(%)	Zn(%)	Ag(g/t)	Au(g/t)	S.G.
88V-12	23.5	25.1	1.6	62	6.36	3.12	3.24	44.0	0.41	4.10
88V-12	25.1	26.1	1.0	62	2.30	1.07	1.23	19.0	0.27	3.40
88V-12	26.1	27.1	1.0	80	19.42	9.32	10.10	108.0	0.75	3.10
88V-12	27.1	28.2	1.1	80	14.29	5.35	8.94	63.0	0.34	3.20
88V-12	28.2	29.2	1.0	62	10.16	3.74	6.42	70.0	0.27	3.60

SECTION: 16_0E POLYGON: 16E3

COMPOSITED ASSAY OF SELECTED INTERVALS

S.G. and length weighted composites:

number of samples	from (m)	to (m)	interval (m)	Pb+Zn (%)	Pb (%)	Zn (%)	Ag (g/t)	Au (g/t)	S.G.
5	23.5	29.2	5.7	9.74	4.23	5.52	57.6	0.40	3.54

Length weighted composites:

number of samples	from (m)	to (m)	interval (m)	Pb+Zn (%)	Pb (%)	Zn (%)	Ag (g/t)	Au (g/t)	S.G.
5	23.5	29.2	5.7	10.14	4.39	5.75	59.1	0.41	3.54

CURRAGH RESOURCES INC.
 VANGORDA PROJECT, FARD, YUKON

DRILLHOLE COMPOSITES SECTION: 16_0E POLYGON: 16E4

hole	from	to	interval	rock code	Pb+Zn	Pb(%)	Zn(%)	Ag(g/t)	Au(g/t)	S.G.
BBV-12	36.8	38.1	1.3	61	10.16	4.42	5.74	56.0	0.75	3.80
BBV-12	38.1	39.6	1.5	61	7.02	3.18	3.84	48.0	0.41	4.00

SECTION: 16_0E POLYGON: 16E4

COMPOSITED ASSAY OF SELECTED INTERVALS

S.G. and length weighted composites:

number of samples	from (m)	to (m)	interval (m)	Pb+Zn (%)	Pb (%)	Zn (%)	Ag (g/t)	Au (g/t)	S.G.
2	36.8	39.6	2.8	8.44	3.74	4.70	51.6	0.56	3.91

Length weighted composites:

number of samples	from (m)	to (m)	interval (m)	Pb+Zn (%)	Pb (%)	Zn (%)	Ag (g/t)	Au (g/t)	S.G.
2	36.8	39.6	2.8	8.48	3.76	4.72	51.7	0.57	3.91

CURRAGH RESOURCES INC.
 VANGORDA PROJECT, FARO, YUKON

DRILLHOLE COMPOSITES SECTION: 16_OE POLYGON: 16E5

hole	from	to	interval	rock code	Pb+Zn	Pb(%)	Zn(%)	Ag(g/t)	Au(g/t)	S.G.
P54V044	17.9	19.5	1.6	61	10.15	2.58	7.57	-1.0	-1.00	4.21

COMPOSITED ASSAY OF SELECTED INTERVALS

S.G. and length weighted composites:

number of samples	from (m)	to (m)	interval (m)	Pb+Zn (%)	Pb (%)	Zn (%)	Ag (g/t)	Au (g/t)	S.G.
1	17.9	19.5	1.6	10.15	2.58	7.57	-1.0	-1.00	4.21

Length weighted composites:

number of samples	from (m)	to (m)	interval (m)	Pb+Zn (%)	Pb (%)	Zn (%)	Ag (g/t)	Au (g/t)	S.G.
1	17.9	19.5	1.6	10.15	2.58	7.57	-1.0	-1.00	4.21

CURRAGH RESOURCES INC.
 VANGORDA PROJECT, FARD, YUKON

DRILLHOLE COMPOSITES SECTION: 16_OE POLYGON: 16E6

hole	from	to	interval	rock code	Pb+Zn	Pb(%)	Zn(%)	Ag(g/t)	Au(g/t)	S.G.
P54V044	40.8	42.3	1.5	31	6.42	1.60	4.82	-1.0	-1.00	3.44
P54V044	42.3	43.2	0.9	31	10.50	2.72	7.78	-1.0	-1.00	3.44

COMPOSITED ASSAY OF SELECTED INTERVALS-----

S.G. and length weighted composites:

number of samples	from (m)	to (m)	interval (m)	Pb+Zn (%)	Pb (%)	Zn (%)	Ag (g/t)	Au (g/t)	S.G.
2	40.8	43.2	2.4	7.95	2.02	5.93	-1.0	-1.00	3.44

Length weighted composites:

number of samples	from (m)	to (m)	interval (m)	Pb+Zn (%)	Pb (%)	Zn (%)	Ag (g/t)	Au (g/t)	S.G.
2	40.8	43.2	2.4	7.95	2.02	5.93	-1.0	-1.00	3.44

CURRAGH RESOURCES INC.
 VANGORDA PROJECT, FARD, YUKON

DRILLHOLE COMPOSITES SECTION: 16_0E POLYGON: 16E7

hole	from	to	interval	rock code	Pb+Zn	Pb(%)	Zn(%)	Ag(g/t)	Au(g/t)	S.G.
88V-17	13.8	15.8	2.0	120	7.25	6.91	0.34	100.0	0.41	3.30

SECTION: 16_0E POLYGON: 16E7

COMPOSITED ASSAY OF SELECTED INTERVALS-----

S.G. and length weighted composites:

number of samples	from (m)	to (m)	interval (m)	Pb+Zn (%)	Pb (%)	Zn (%)	Ag (g/t)	Au (g/t)	S.G.
1	13.8	15.8	2	7.25	6.91	0.34	100.0	0.41	3.30

Length weighted composites:

number of samples	from (m)	to (m)	interval (m)	Pb+Zn (%)	Pb (%)	Zn (%)	Ag (g/t)	Au (g/t)	S.G.
1	13.8	15.8	2	7.25	6.91	0.34	100.0	0.41	3.30

CURRAGH RESOURCES INC.
 VANGORDA PROJECT, FARD, YUKON

DRILLHOLE COMPOSITES SECTION: 16_0E POLYGON: 16E8

hole	from	to	interval	rock code	Pb+Zn	Pb(%)	Zn(%)	Ag(g/t)	Au(g/t)	S.G.
88V-17	17.4	18.3	0.9	61	6.43	3.12	3.31	39.0	0.55	3.90
88V-17	18.3	19.2	0.9	61	2.82	1.04	1.78	19.0	0.48	3.00
88V-17	19.2	21.0	1.8	61	12.83	5.35	7.48	93.0	0.69	4.30
88V-17	21.0	22.5	1.5	61	7.64	3.94	3.70	47.0	1.78	3.70
88V-17	22.5	23.2	0.7	61	7.44	3.35	4.09	45.0	2.06	3.60

SECTION: 16_0E POLYGON: 16E8

COMPOSITED ASSAY OF SELECTED INTERVALS-----

S.G. and length weighted composites:

number of samples	from (m)	to (m)	interval (m)	Pb+Zn (%)	Pb (%)	Zn (%)	Ag (g/t)	Au (g/t)	S.G.
5	17.4	23.2	5.8	8.66	3.88	4.78	58.2	1.07	3.80

Length weighted composites:

number of samples	from (m)	to (m)	interval (m)	Pb+Zn (%)	Pb (%)	Zn (%)	Ag (g/t)	Au (g/t)	S.G.
5	17.4	23.2	5.8	8.29	3.73	4.56	55.4	1.08	3.80

CURRAGH RESOURCES INC.
 VANGORDA PROJECT, FARO, YUKON

DRILLHOLE COMPOSITES SECTION: 16_0E POLYGON: 16E9

hole	from	to	interval	rock code	Pb+Zn	Pb(%)	Zn(%)	Ag(g/t)	Au(g/t)	S.G.
88V-17	33.5	34.7	1.2	100	10.18	9.32	0.86	81.0	4.80	2.70
88V-17	34.7	36.0	1.3	100	9.51	8.79	0.72	78.0	0.89	2.70

SECTION: 16_0E POLYGON: 16E9

COMPOSITED ASSAY OF SELECTED INTERVALS

S.G. and length weighted composites:

number of samples	from (m)	to (m)	interval (m)	Pb+Zn (%)	Pb (%)	Zn (%)	Ag (g/t)	Au (g/t)	S.G.
2	33.5	36	2.5	9.83	9.04	0.79	79.4	2.77	2.70

Length weighted composites:

number of samples	from (m)	to (m)	interval (m)	Pb+Zn (%)	Pb (%)	Zn (%)	Ag (g/t)	Au (g/t)	S.G.
2	33.5	36	2.5	9.83	9.04	0.79	79.4	2.77	2.70

CURRAGH RESOURCES INC.
 VANGORDA PROJECT, FARO, YUKON

DRILLHOLE COMPOSITES SECTION: 16_0E POLYGON: 16E10

hole	from	to	interval	rock code	Pb+Zn	Pb(%)	Zn(%)	Ag(g/t)	Au(g/t)	S.G.
88V-14	15.9	17.6	1.7	61	10.59	3.10	7.49	62.0	0.14	3.90
88V-14	17.6	19.2	1.6	61	6.52	3.34	3.18	56.0	1.10	3.70

SECTION: 16_0E POLYGON: 16E10

COMPOSITED ASSAY OF SELECTED INTERVALS-----

S.G. and length weighted composites:

number of samples	from (m)	to (m)	interval (m)	Pb+Zn (%)	Pb (%)	Zn (%)	Ag (g/t)	Au (g/t)	S.G.
2	15.9	19.2	3.3	8.67	3.21	5.46	59.2	0.59	3.80

Length weighted composites:

number of samples	from (m)	to (m)	interval (m)	Pb+Zn (%)	Pb (%)	Zn (%)	Ag (g/t)	Au (g/t)	S.G.
2	15.9	19.2	3.3	8.62	3.22	5.40	59.1	0.61	3.80

CURRAGH RESOURCES INC.
 VANGORDA PROJECT, FARO, YUKON

DRILLHOLE COMPOSITES SECTION: 16_0E POLYGON: 16E11

hole	from	to	interval	rock code	Pb+Zn	Pb(%)	Zn(%)	Ag(g/t)	Au(g/t)	S.G.
88V-14	27.6	29.4	1.8	41	6.57	3.57	3.00	49.0	0.82	3.40

SECTION: 16_0E POLYGON: 16E11

COMPOSITED ASSAY OF SELECTED INTERVALS

S.G. and length weighted composites:

number of samples	from (m)	to (m)	interval (m)	Pb+Zn (%)	Pb (%)	Zn (%)	Ag (g/t)	Au (g/t)	S.G.
1	27.6	29.4	1.8	6.57	3.57	3.00	49.0	0.82	3.40

Length weighted composites:

number of samples	from (m)	to (m)	interval (m)	Pb+Zn (%)	Pb (%)	Zn (%)	Ag (g/t)	Au (g/t)	S.G.
1	27.6	29.4	1.8	6.57	3.57	3.00	49.0	0.82	3.40

CURRAGH RESOURCES INC.
VANGORDA PROJECT, FARO, YUKON

DRILLHOLE COMPOSITES SECTION: 17_0E POLYGON: 17E1

hole	from	to	interval	rock code	Pb+Zn	Pb(%)	Zn(%)	Ag(g/t)	Au(g/t)	S.G.
87V-15	9.4	10.8	1.4	62	9.58	5.22	4.36	67.0	1.03	3.90
87V-15	10.8	12.2	1.4	62	9.33	5.14	4.19	69.0	0.75	3.80
87V-15	12.2	13.4	1.2	62	6.60	3.44	3.16	50.0	1.41	4.40
87V-15	13.4	14.4	1.0	62	19.71	7.91	11.80	117.0	1.58	4.10
87V-15	14.4	15.8	1.4	120	4.06	1.58	2.48	24.0	0.27	3.10
87V-15	15.8	17.1	1.3	61	13.48	4.94	8.54	81.0	1.17	4.50
87V-15	17.1	18.6	1.5	61	13.67	4.77	8.90	77.0	0.96	4.40
87V-15	18.6	19.9	1.3	61	16.19	6.51	9.68	99.0	1.27	4.40
87V-15	19.9	20.8	0.9	61	23.00	12.60	10.40	140.0	1.54	4.60
87V-15	20.8	21.9	1.1	61	25.30	15.10	10.20	142.0	1.34	4.70
87V-15	21.9	23.2	1.3	61	18.12	8.02	10.10	91.0	1.17	4.70

SECTION: 17_0E POLYGON: 17E1

COMPOSITED ASSAY OF SELECTED INTERVALS-----

S.G. and length weighted composites:

number of samples	from (m)	to (m)	interval (m)	Pb+Zn (%)	Pb (%)	Zn (%)	Ag (g/t)	Au (g/t)	S.G.
11	9.4	23.2	13.8	14.35	6.72	7.63	86.1	1.13	4.21

Length weighted composites:

number of samples	from (m)	to (m)	interval (m)	Pb+Zn (%)	Pb (%)	Zn (%)	Ag (g/t)	Au (g/t)	S.G.
11	9.4	23.2	13.8	13.84	6.46	7.38	83.4	1.10	4.21

CURRAGH RESOURCES INC.
 VANGORDA PROJECT, FARO, YUKON

DRILLHOLE COMPOSITES SECTION: 17_0E POLYGON: 17E2

hole	from	to	interval	rock code	Pb+Zn	Pb(%)	Zn(%)	Ag(g/t)	Au(g/t)	S.G.
88V-19	14.3	15.9	1.6	61	7.67	3.42	4.25	32.0	0.55	4.10
88V-19	15.9	17.2	1.3	61	5.52	2.58	2.94	26.0	0.89	4.10
88V-19	17.2	18.4	1.2	61	10.18	4.28	5.90	43.0	0.27	3.80

SECTION: 17_0E POLYGON: 17E2

COMPOSITED ASSAY OF SELECTED INTERVALS-----

S.G. and length weighted composites:

number of samples	from (m)	to (m)	interval (m)	Pb+Zn (%)	Pb (%)	Zn (%)	Ag (g/t)	Au (g/t)	S.G.
3	14.3	18.4	4.1	7.67	3.39	4.28	33.1	0.58	4.01

Length weighted composites:

number of samples	from (m)	to (m)	interval (m)	Pb+Zn (%)	Pb (%)	Zn (%)	Ag (g/t)	Au (g/t)	S.G.
3	14.3	18.4	4.1	7.72	3.41	4.32	33.3	0.58	4.01