

DDH: 65009

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													S.G. U.R.
FROM	TO						CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	
345.0	350.0	70114	5.0	.0	****	2.86	.24	.26	.57	6.00				5	5	11	.21			.12
350.0	355.0	70115	5.0	.0	****	3.02	.24	.86	3.01	9.00				6	17	24	.13			.14
355.0	360.0	70116	5.0	.0	****	3.25	.07	3.13	3.87	35.00				6	17	24	4.39			.14
360.0	365.0	70117	5.0	.0	****	4.71	.19	5.00	6.52	70.00				6	17	24	16.14			.14
365.0	370.0	70118	5.0	.0	****	4.44	.21	5.03	7.28	62.00				6	17	24	.17			.14
370.0	375.0	70119	5.0	.0	****	4.15	.42	4.87	6.89	57.00				11	21	33	1.83			.16
375.0	380.0	70120	5.0	.0	****	4.29	.45	3.04	5.44	46.00				11	21	33	8.32			.16
380.0	385.0	70121	5.0	.0	****	4.54	.13	4.72	7.45	57.00				11	21	33	3.98			.16
385.0	390.0	70122	5.0	.0	****	4.46	.09	5.18	6.82	49.00				11	21	33	.05			.16
390.0	395.0	70123	5.0	.0	****	4.16	.12	3.72	5.92	30.00				11	25	37	.07			.12
395.0	400.0	70124	5.0	.0	****	4.26	.13	5.63	5.02	58.00				11	25	37	.07			.12
400.0	405.0	70125	5.0	.0	****	4.46	.57	5.50	7.81	54.00				11	25	37	.09			.12
405.0	410.0	70126	5.0	.0	****	4.63	.25	5.30	7.21	44.00				11	25	37	.14			.12
410.0	415.0	70127	5.0	.0	****	4.58	.21	6.01	7.28	47.00				7	25	32	.07			.14
415.0	420.0	70128	5.0	.0	****	4.76	.23	4.71	5.21	47.00				7	25	32	9.08			.14
420.0	425.0	70129	5.0	.0	****	4.53	.22	2.28	1.92	24.00				7	25	32	.07			.14
425.0	430.0	70130	5.0	.0	****	3.67	.28	5.62	13.10	54.00				7	25	32	1.19			.14
430.0	435.0	70131	5.0	.0	****	2.91	.09	1.46	4.13	26.00				3	2	6	.22			.05
435.0	440.0	70132	5.0	.0	****	3.30	.06	17.60	2.51	82.00				3	2	6	.15			.05
440.0	445.0	70133	5.0	.0	****	2.75	.06	1.33	2.68	23.00				3	2	6	.17			.05
445.0	450.0	70134	5.0	.0	****	2.64	.05	1.38	2.76	24.00				3	2	6	.16			.05
450.0	455.0	70135	5.0	.0	****	3.04	.09	3.92	3.67	67.00				6	6	12	.25			.06
455.0	460.0	70136	5.0	.0	****	3.08	.09	9.11	5.68	139.00				6	6	12	.18			.06
460.0	465.0	70137	5.0	.0	****	3.26	.36	1.53	4.51	36.00				6	6	12	.21			.06
465.0	472.0	70138	7.0	.0	****	2.85	.13	1.37	3.33	29.00				6	6	12	.18			.06

DDH: 66-03

---DEPTHS---		SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	---ASSAYS---							S.G. W.R.	
FROM	TO											Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %		Ba %
548.8	553.0	70219	4.2	.0	2C01	2.82	.10	.56	1.46	7.10		5	8	14	.31					.10
553.0	558.0	70220	5.0	.0	2D4 ³³	3.30	.14	2.49	8.93	31.50		5	8	14	.09					.10
558.0	563.0	70221	5.0	.0	2D4	3.33	.18	3.56	11.43	47.20		5	8	14	.10					.10
563.0	568.0	70222	5.0	.0	2F49	3.87	.32	4.38	8.13	71.60		5	8	14	.13					.10
568.0	573.0	70223	5.0	.0	2F49	4.88	.31	6.29	6.43	86.80		8	23	31	.08					.40
573.0	578.0	70224	5.0	.0	2F49 ⁵⁰	4.95	.27	7.30	7.46	98.90		8	23	31	.06					.40
578.0	583.0	70225	5.0	.0	2F46	4.95	.20	5.69	6.36	99.70		8	23	31	.29					.40
583.0	586.0	70226	3.0	.0	2F49	4.46	.34	7.17	7.14	89.70		8	23	31	.08					.40
586.0	590.6	70227	4.6	.0	2A01	2.95	.11	1.20	.92	32.80		8	23	31	2.44					.40
590.6	595.0	70228	4.4	.0	2A01	2.97	.12	1.90	1.80	30.80		4	4	8	3.02					.16
595.0	600.0	70229	5.0	.0	2B01 ³²	3.13	.07	1.72	1.68	30.90		4	4	8	4.83					.16
600.0	605.0	70230	5.0	.0	2D01	3.07	.07	1.24	1.96	13.20		4	4	8	3.29					.16
605.0	610.0	70231	5.0	.0	2B6	2.94	.02	.44	.86	7.00		4	4	8	4.32					.16
610.0	615.0	70232	5.0	.0	2D61 ³²	3.01	.05	.98	1.40	18.80		4	7	12	3.77					.10
615.0	620.0	70233	5.0	.0	2D61	2.90	.09	1.20	3.01	26.90		4	7	12	2.69					.10
620.0	624.0	70234	4.0	.0	2D0	3.05	.11	1.48	4.57	35.30		4	7	12	.33					.10
624.0	629.0	70235	5.0	.0	2D41 ³²	3.93	.22	9.45	9.51	152.00		4	7	12	.15					.10
629.0	634.0	70236	5.0	.0	2D41 ³²	4.15	.15	5.50	7.80	72.70					.12					
634.0	639.0	70237	5.0	.0	2C01	4.15	.07	.50	.70	4.10					.12					
639.0	644.0	70238	5.0	.0	2D91	4.15	.24	2.60	2.70	20.60					.12					
644.0	649.0	70239	5.0	.0	2D91	4.15	.19	3.60	4.80	20.60					.12					
649.0	654.0	70240	5.0	.0	2D91 ⁵⁰	4.80	.21	2.86	3.56	29.70		15	27	42	.09					.19
654.0	659.0	70241	5.0	.0	2E91	4.56	.29	2.30	.94	23.90		15	27	42	.04					.19
659.0	664.0	70242	5.0	.0	2A4&	4.29	.33	1.06	2.29	15.80		15	27	42	.03					.19
664.0	669.0	70243	5.0	.0	2A4& ⁵⁰	3.23	.23	2.41	1.65	13.10		15	27	42	.05					.19
669.0	674.0	70244	5.0	.0	2E19	4.26	.32	1.68	1.42	23.80		10	31	41	.04					.12
674.0	679.0	70245	5.0	.0	2E19	4.57	.32	2.00	3.90	17.10		10	31	41	.02					.12
679.0	684.0	70246	5.0	.0	2A41	4.58	.16	3.42	4.18	67.30		10	31	41	.04					.12
684.0	689.0	70247	5.0	.0	2A41 ²¹	4.26	.22	2.43	2.37	14.20		10	31	41	.06					.12
689.0	694.0	70248	5.0	.0	2A41	4.80	.11	3.30	4.81	17.40		3	16	19	.02					.06
694.0	699.0	70249	5.0	.0	2A41	3.32	.23	1.88	5.79	29.90		3	16	19	.09					.06
699.0	704.0	70250	5.0	.0	2A01	2.81	.07	1.36	2.54	30.40		3	16	19	.21					.06
704.0	709.0	70251	5.0	.0	2A41 ²¹	2.93	.05	.90	3.51	30.20		3	16	19	.23					.06
709.0	714.0	70252	5.0	.0	2A41	2.78	.06	1.12	3.09	17.20		2	15	18	.22					.04
714.0	719.0	70253	5.0	.0	2A41	2.68	.09	1.14	4.63	54.80		2	15	18	.34					.04
719.0	724.0	70254	5.0	.0	2A41	4.25	.34	5.05	9.02	86.20		2	15	18	.06					.04
724.0	729.0	70255	5.0	.0	2A41 ²¹	4.13	.13	2.56	5.79	29.60		2	15	18	.10					.04
729.0	734.0	70256	5.0	.0	2A41	3.01	.17	1.80	3.93	24.60		2	15	18	.21					.04
734.0	739.0	70257	5.0	.0	2A01	2.90		.20	1.30	6.20		2	15	18	.20					.04

DDH: 66-05

---DEPTHS---					---ASSAYS---															
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
489.0	494.0	70320	5.0	2A0	3.04	.06	.34	.96	9.20			3	7	10	.11		.07			
494.0	499.0	70321	5.0	2A0	3.20	.10	.40	.92	10.80			3	7	10	.13		.07			
499.0	504.0	70322	5.0	2A0	3.04	.08	1.36	1.77	18.20			3	7	10	.07		.07			
504.0	509.0	70323	5.0	2A0	2.52	.03	.88	2.86	13.20			3	7	10	.32		.07			
509.0	514.0	70324	5.0	2A4	3.09	.05	1.28	4.00	22.10			4	11	16	.19		.06			
514.0	519.0	70325	5.0	2F4	4.07	.09	5.21	9.11	65.20			4	11	16	.09		.06			
519.0	524.0	70326	5.0	2C0	2.86	.16	1.68	2.20	33.40			4	11	16	.34		.06			
524.0	529.0	70327	5.0	2C0	3.17	.18	.96	1.98	31.10			4	11	16	.38		.06			
529.0	534.0	70328	5.0	2D0	3.43	.14	2.79	7.00	50.20			4	8	13	.16		.04			
534.0	539.0	70329	5.0	2E4	3.21	.21	1.94	3.93	35.30			4	8	13	.16		.04			
539.0	544.0	70330	5.0	2A0	2.82	.10	.74	2.03	14.20			4	8	13	.19		.04			
544.0	549.0	70331	5.0	2A0	2.88	.04	1.10	1.82	29.30			4	8	13	.20		.04			
549.0	554.0	70332	5.0	2A0	2.60	.14	2.08	1.36	29.30			4	8	13	.20		.04			

÷6 2.31 4.70 (7.0)
 ÷4 2.66 5.07 (7.7)
 ÷2 3.25 6.56
 2.72 5.1

DDH: 66-06

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	---ASSAYS---					S.G. W.R.			
FROM	TO												Po %	Py %	TOT Fe %	BAO %	Hg %		Mn %	As %	Ba %
423.5	428.3	70337	4.8	.0	2D34	3.96	16	2.80	7.90	109.70			3	17	20	.20					.06
437.0	441.0	70339	4.0	.0	2H10	3.14	.01	2.50	2.60	69.90			12	18	30	.20					.09
456.0	460.0	70341	4.0	.0	2E00	3.10	.16	.93	3.15	20.40			4	22	26	.18					.07
460.0	465.0	70342	5.0	.0	2D48	3.28	.19	2.89	9.07	40.10			4	22	26	.20					.07
465.0	470.0	70343	5.0	.0	2E40	4.60	.28	2.84	4.91	52.60			4	22	26	.06					.07
470.0	475.0	70344	5.0	.0	2E00	4.56	.19	.35	1.36	8.70			4	22	26	.07					.07
475.0	480.0	70345	5.0	.0	2D40	4.00	.27	3.29	6.91	29.80			4	22	26	.10					.07
480.0	485.0	70346	5.0	.0	2D00	3.71	.06	1.35	3.38	15.60			3	26	30	.12					.09
485.0	490.0	70347	5.0	.0	2E10	3.59	.04	1.00	2.80	14.60			3	26	30	.09					.09
490.0	495.0	70348	5.0	.0	2E81	4.04	.29	.30	.84	19.10			3	26	30	.04					.09
495.0	500.0	70349	5.0	.0	2E81	3.89	.29		.86	7.10			3	26	30	.03					.09
500.0	505.0	70350	5.0	.0	2E81	4.06	.31	.69	1.66	9.30			3	26	30	.03					.15
505.0	510.0	70351	5.0	.0	2E81	4.10	.22	.51	1.04	6.60			3	26	30	.02					.15
510.0	515.0	70352	5.0	.0	2E81	3.93	.23	.93	1.92	13.70			3	26	30	.05					.15
515.0	520.0	70353	5.0	.0	2A40	3.81	.09	3.53	7.29	146.00			3	26	30	.10					.15
520.0	524.0	70354	4.0	.0	2A40	3.22	.14	3.26	4.60	55.20			4	17	21	.17					.11
524.0	529.0	70355	5.0	.0	2C3	3.32	.23	1.89	1.64	40.50			4	17	21	.11					.11
529.0	534.0	70356	5.0	.0	2D00	3.69	.16	2.90	2.35	46.70			4	17	21	.10					.11
534.0	539.0	70357	5.0	.0	2C30	3.74	.14	.56	1.56	14.00			4	17	21	.08					.11
539.0	544.0	70358	5.0	.0	2C3	3.88	.12	.55	1.80	11.50			2	27	29	.05					.06
544.0	549.0	70359	5.0	.0	2C30	4.57	.07	.10	1.74	3.90			2	27	29	.04					.06
549.0	554.0	70360	5.0	.0	2D3	4.17	.10	1.63	4.58	11.30			2	27	29	.05					.06
554.0	559.0	70361	5.0	.0	2D3	4.29	.25	2.22	2.84	22.00			2	27	29	.03					.06
559.0	564.0	70362	5.0	.0	2D48	3.71	.07	4.43	7.87	16.00			2	21	24	.06					.03
564.0	569.0	70363	5.0	.0	2D3	3.94	.08	1.82	5.80	12.10			2	21	24	.06					.03
569.0	574.0	70364	5.0	.0	2D45	3.55	.10	3.10	11.22	12.50			2	21	24	.14					.03
574.0	579.0	70365	5.0	.0	2D43	4.07	.05	4.82	9.17	16.10			2	21	24	.05					.03
579.0	584.0	70366	5.0	.0	2D48	3.75	.07	4.65	10.19	16.50			3	23	26	.06					.05
584.0	589.0	70367	5.0	.0	2D48	3.62	.04	5.66	11.10	12.70			3	23	26	.09					.05
589.0	594.0	70368	5.0	.0	2E41	4.00	.04	2.06	6.18	7.60			3	23	26	.06					.05
594.0	599.0	70369	5.0	.0	2E41	4.25	.06	2.14	4.90	8.20			3	23	26	.03					.05
599.0	604.0	70370	5.0	.0	2D43	3.70	.05	3.74	9.66	21.70			3	17	21	.10					.04
604.0	609.0	70371	5.0	.0	2D43	3.44	.06	2.00	7.14	16.00			3	17	21	.17					.04
609.0	614.0	70372	5.0	.0	2E48	4.22	.04	1.76	5.56	20.30			3	17	21	.08					.04
614.0	619.0	70373	5.0	.0	2D00	3.13	.18	2.69	5.95	73.70			3	17	21	.27					.04
619.0	622.8	70374	3.8	.0	2D00	3.07	.07	1.33	4.01	22.60			3	17	21	.32					.04

Waste
inferred

White

33

50

33

40

40

40

21

21

21

21

21

21

21

21

50

21

21

DDH: 66-07

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													S.G. W.R.
FROM	TO						CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	
588.0	593.0	70382	5.0	.0	2E48	4.18	.07	5.35	6.20	54.30				7	22	30	.16		.13	
593.0	598.0	70383	5.0	.0	2E48	4.16	.09	2.88	3.87	26.00				7	22	30	.10		.13	
598.0	603.0	70384	5.0	.0	2E30	3.93	50 .07	1.78	2.30	19.50				7	22	30	.08		.13	
603.0	608.0	70385	5.0	.0	2D40	3.60	.17	3.26	5.90	15.10				7	22	30	.07		.13	
608.0	613.0	70386	5.0	.0	2D49	3.97	.21	3.84	9.76	13.80				4	25	30	.05		.16	
613.0	618.0	70387	5.0	.0	2E89	4.32	.25	1.18	2.84	7.80				4	25	30	.02		.16	
618.0	623.0	70388	5.0	.0	2D4	4.84	50 .13	4.13	8.36	10.00				4	25	30	.02		.16	
623.0	628.0	70389	5.0	.0	2F41	4.39	.06	4.51	12.51	13.60				4	25	30	.05		.16	
628.0	633.0	70390	5.0	.0	2D40	3.39	.02	3.97	8.36	20.00				4	20	24	.06		.04	
633.0	638.0	70391	5.0	.0	2D40	4.01	50 .02	2.78	6.58	14.00				4	20	24	.09		.04	
638.0	643.0	70392	5.0	.0	2E40	4.55	.16	8.34	19.56	47.00				4	20	24	.06		.04	
643.0	648.0	70393	5.0	.0	2F40	3.67	.06	3.78	10.87	27.40				4	20	24	.17		.04	
648.0	658.0	70394	10.0	.0	2C0	3.03	.06	.96	2.24	19.20				3	13	17	.27		.03	
658.0	663.0	70395	5.0	.0	2C0	3.20	21 .16	.35	2.36	9.50				3	13	17	.20		.03	
663.0	668.0	70396	5.0	.0	2A30	3.24	.04	.25	1.66	18.50				3	13	17	.17		.03	
668.0	673.0	70397	5.0	.0	2A30	3.40	21 .04	1.06	1.46	29.00				3	13	17	.23		.04	
673.0	678.0	70398	5.0	.0	2D00	2.95	.12	1.76	4.33	22.70				3	13	17	.22		.04	

DDH: 66-11

---DEPTHS---					-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
551.0	556.0	70521	5.0	.0	2C39	3.36	.17	.94	1.43	19.30		6	13	20	.10		.06			
556.0	561.0	70522	5.0	.0	2C35	3.09	.17	1.11	2.23	23.30		6	13	20	.16		.06			
561.0	566.0	70523	5.0	.0	2D35	3.25	21 .05	2.19	4.35	26.80		4	13	18	.15		.04			
566.0	571.0	70524	5.0	.0	2C50	3.12	.16	.79	2.06	16.40		4	13	18	.21		.04			
571.0	576.0	70525	5.0	.0	2C50	3.37	.05	1.07	1.62	21.30		4	13	18	.16		.04			
576.0	581.0	70526	5.0	.0	0090	2.94	21 .10	1.16	3.28	18.90		4	13	18	.12		.04			
581.0	586.0	70527	5.0	.0	2C0	3.08	.06	1.12	1.93	18.80		5	7	12	.24		.02			
586.0	591.0	70528	5.0	.0	2C00	2.87	.14	.68	2.07	33.10		5	7	12	.34		.02			
591.0	596.0	70529	5.0	.0	2C90	2.94	21 .26	5.53	1.27	202.90		5	7	12	.22		.02			
596.0	601.0	70530	5.0	.0	2C00	3.01	.13	1.63	2.68	37.20		5	7	12	.25		.02			

DDH: 66-46

---DEPTHS---		SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														S.G. W.R.
FROM	TO					CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %	
735.0	740.0	70855	5.0	.0	2D4&	2.92	.27	2.87	7.41	40.50				7	9	16	.16			.03
740.0	745.0	70856	5.0	.0	2A97	3.18	.19	.84	2.52	20.80				7	9	16	.22			.03
745.0	750.0	70857	5.0	.0	2C79	3.03	21.22	.25	1.55	13.80				7	9	16	.33			.03
750.0	755.0	70858	5.0	.0	2C79	2.99	.35	.04	.31	21.20				15	1	16	.29			.02
755.0	760.0	70859	5.0	.0	2C79	2.97	.27	.60	1.27	23.10				15	1	16	.20			.02

DDH: 66-47

					-----ASSAYS-----															
---DEPTHS---	SAMPLE	INT.	REC.	ROCK	S.G.	CU	Pb	Zn	Ag(AA)	Ag(FA)	Au(FA)	Po	Py	TOT	BAO	Hg	Mn	As	Ba	S.G.
FROM	TO	NO.		UNIT	PULP	%	%	%	g/mT	g/mT	g/mT	%	%	Fe	%	%	%	%	%	W.R.
590.0	595.0	70867	5.0	.0	2L40	2.90	.19	1.41	.10	219.90				3	4	7	.12			.05
595.0	600.0	70868	5.0	.0	2L40	2.73	.09	.56	.09	49.00				3	4	7	.14			.05
600.0	605.0	70869	5.0	.0	2L40	2.78	.02	.04	.09	1.20				3	4	7	.16			.05
605.0	610.0	70870	5.0	.0	2D00	3.07	.12	1.75	3.53	14.40				3	4	7	.12			.05
610.0	615.0	70871	5.0	.0	2D00	3.16	.31	2.50	4.41	32.20				5	7	12	.14			.04
615.0	620.0	70872	5.0	.0	2B9&	3.00	.20	.96	1.57	27.00				5	7	12	.22			.04

DDH: 66-49

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													S.G. W.R.
FROM	TO						CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe %	BAO %	Hg %	Mn %	As %	
555.0	560.0	70877	5.0	.0	2H43	3.22	.16	2.56	3.21	41.00				15	13	29	.19			.25
560.0	565.0	70878	5.0	.0	2H43	4.87	70.23	6.00	7.66	78.40				15	13	29	.17			.25
565.0	570.0	70879	5.0	.0	2H49	4.47	.29	8.79	9.53	117.70				15	13	29	.10			.25
570.0	575.0	70880	5.0	.0	2H49	4.71	.42	7.48	8.09	98.80				12	14	26	1.14			.36
575.0	580.0	70881	5.0	.0	2D47	3.73	.18	3.84	4.04	59.10				12	14	26	1.84			.36
580.0	585.0	70882	5.0	.0	2L14	3.05	70.14	2.73	2.83	42.20				12	14	26	3.09			.36
585.0	590.0	70883	5.0	.0	2H49	4.53	.27	7.08	9.26	100.30				12	14	26	.62			.36
590.0	595.0	70884	5.0	.0	2G49	4.68	60.20	4.57	6.88	41.80				5	20	25	7.31			.13
595.0	600.0	70885	5.0	.0	2E11	5.07	.17	1.31	1.94	17.30				5	20	25	.34			.13
600.0	605.0	70886	5.0	.0	2B49	2.76	32.22	2.07	3.58	46.70				5	20	25	.26			.13
605.0	610.0	70887	5.0	.0	2B49	2.99	.23	3.69	2.01	67.60				5	20	25	.31			.13
610.0	615.0	70888	5.0	.0	2B0	2.76	32.09	.72	1.97	15.10				9	20	30	.41			.10
615.0	620.0	70889	5.0	.0	2B49	3.40	.30	2.14	3.60	37.90				9	20	30	.38			.10
620.0	625.0	70890	5.0	.0	2E91	4.84	50.47	1.40	1.31	21.90				9	20	30	.02			.10
625.0	630.0	70891	5.0	.0	2E91	5.15	.42	2.82	1.16	21.60				9	20	30	.02			.10
630.0	635.0	70892	5.0	.0	2E91	4.77	.42	3.93	3.77	26.50				5	34	40	.02			.17
635.0	640.0	70893	5.0	.0	2E91	4.46	50.24	2.64	5.06	20.60				5	34	40	.03			.17
640.0	645.0	70894	5.0	.0	2F49	4.71	.46	5.28	4.63	35.90				5	34	40	.02			.17
645.0	650.0	70895	5.0	.0	2F4	4.93	.12	4.30	7.12	24.60				5	34	40	.02			.17
650.0	655.0	70896	5.0	.0	2A49	3.54	.24	2.24	4.61	21.10				5	10	16	.18			.05
655.0	660.0	70897	5.0	.0	2A4	2.72	.05	1.09	3.23	23.70				5	10	16	.32			.05
660.0	665.0	70898	5.0	.0	2A4	2.92	21.08	1.25	3.13	34.80				5	10	16	.23			.05
665.0	670.0	70899	5.0	.0	2D91	3.49	.28	2.03	4.72	51.10				5	10	16	.17			.05
670.0	675.0	70900	5.0	.0	2D01	3.27	.19	1.57	3.11	32.10				5	5	11	.28			.08
675.0	680.0	70901	5.0	.0	2A41	3.02	21.10	2.47	2.51	53.40				5	5	11	.15			.08
680.0	685.0	70902	5.0	.0	2A4	2.88	.10	1.26	3.19	29.20				5	5	11	.16			.08

DDH: 66-52

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													S.G. W.R.
FROM	TO						CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	
515.0	520.0	70907	5.0	.0	2H49	4.48	.38	5.17	7.34	58.00				20	6	27	.19		.11	
520.0	525.0	70908	5.0	.0	2D49	4.05	.38	6.34	9.32	69.80				20	6	27	.17		.11	
525.0	530.0	70909	5.0	.0	2D0 33	2.59	.09	2.27	6.05	31.10				20	6	27	.15		.11	
530.0	535.0	70910	5.0	.0	2D40	3.93	.21	5.31	8.11	71.60				8	25	33	.17		.11	
535.0	540.0	70911	5.0	.0	2F4	4.67	.20	5.68	7.85	56.00				8	25	33	.10		.11	
540.0	545.0	70912	5.0	.0	2F4 50	4.78	.17	6.42	8.14	64.80				8	25	33	1.67		.11	
545.0	550.0	70913	5.0	.0	2F4	4.72	.07	6.71	9.67	62.30				8	25	33	.07		.11	
550.0	555.0	70914	5.0	.0	2F4	5.14	.16	7.62	7.49	71.20				2	30	33	.09		.08	
555.0	560.0	70915	5.0	.0	2F4 50	5.30	.07	7.68	9.39	55.70				2	30	33	.05		.08	
560.0	565.0	70916	5.0	.0	2F4	4.88	.10	7.25	9.12	53.50				2	30	33	.08		.08	
565.0	570.0	70917	5.0	.0	2G42	3.46	.26	6.60	7.80	52.60				2	30	33	12.13		.08	
570.0	575.0	70918	5.0	.0	2F4 60	5.20	.06	6.84	9.79	54.10				4	24	28	.16		.11	
575.0	580.0	70919	5.0	.0	2F40	4.72	.10	7.85	8.81	72.10				4	24	28	6.34		.11	
580.0	585.0	70920	5.0	.0	2F46	4.90	.16	10.28	12.02	114.00				4	24	28	4.67		.11	
585.0	590.0	70921	5.0	.0	2G42 60	5.00	.09	8.26	9.06	95.40				4	24	28	19.48		.11	
590.0	595.0	70922	5.0	.0	2G42	4.57	.29	4.87	4.74	53.70				4	30	35	14.28		.09	
595.0	600.0	70923	5.0	.0	2F40	5.25	.17	3.72	5.23	39.30				4	30	35	.25		.09	
600.0	605.0	70924	5.0	.0	2F40 50	4.79	.08	3.95	7.13	38.00				4	30	35	.13		.09	
605.0	610.0	70925	5.0	.0	2F40	4.63	.08	5.15	7.43	45.80				4	30	35	.07		.09	
610.0	615.0	70926	5.0	.0	2A00	2.91	.04	.94	2.31	17.20				3	2	6	.50		.04	
615.0	620.0	70927	5.0	.0	2B4 21	3.11	.11	1.72	3.32	34.40				3	2	6	.35		.04	
620.0	625.0	70928	5.0	.0	2B40	3.04	.08	1.18	2.80	24.90				3	2	6	.33		.04	
625.0	630.0	70929	5.0	.0	2A00	2.96	.10	.36	.56	9.90				3	2	6	.21		.04	
630.0	635.0	70930	5.0	.0	1D4 Waste	2.64	.20	.23	.13	65.80				3	2	5	.14		.07	
635.0	639.0	70931	4.0	.0	1D4	2.79	.05	.02	.22	3.40				3	2	5	.19		.07	

DDH: 66022

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													S.G. W.R.
FROM	TO						CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe %	BAO %	Hg %	Mn %	As %	
215.0	220.0	70556	5.0	.0	****	3.10	.18	.23	.76	10.00			5	15	21	.39			.12	
220.0	225.0	70557	5.0	.0	****	3.79	.06	.64	3.30	15.00			5	15	21	.86			.12	
225.0	230.0	70558	5.0	.0	****	3.90	.22	3.24	3.39	66.00			5	15	21	9.37			.12	
230.0	235.0	70559	5.0	.0	****	3.65	.24	2.48	2.65	68.00			5	15	21	6.46			.12	
235.0	240.0	70560	5.0	.0	****	3.59	.38	4.99	3.62	126.00			6	8	15	7.11			.13	
240.0	245.0	70561	5.0	.0	****	3.09	.22	1.52	.56	86.00			6	8	15	3.19			.13	
245.0	255.0	70562	10.0	.0	****	3.32	.41	3.04	2.38	75.00			6	8	15	6.43			.13	
255.0	260.0	70563	5.0	.0	****	4.19	.24	4.12	3.79	76.00			5	18	23	13.18			.20	
260.0	265.0	70564	5.0	.0	****	4.76	.19	3.14	3.82	42.00			5	18	23	9.14			.20	
265.0	270.0	70565	5.0	.0	****	4.51	.08	4.09	5.26	63.00			5	18	23	33.17			.20	
270.0	275.0	70566	5.0	.0	****	4.78	.08	6.52	7.19	112.00			5	18	23	36.66			.20	
275.0	280.0	70567	5.0	.0	****	4.92	.08	5.00	5.71	66.00			4	25	29	24.12			.10	
280.0	285.0	70568	5.0	.0	****	4.80	.10	4.93	6.93	68.00			4	25	29	28.49			.10	
285.0	290.0	70569	5.0	.0	****	4.63	.18	2.56	4.76	42.00			4	25	29	15.67			.10	
290.0	295.0	70570	5.0	.0	****	4.85	.19	2.07	1.97	27.00			4	25	29	2.59			.10	
295.0	300.0	70571	5.0	.0	****	4.65	.02	3.54	7.56	35.00			2	33	36	27.63			.02	
300.0	305.0	70572	5.0	.0	****	4.81	.16	1.38	1.06	21.00			2	33	36	1.22			.02	
305.0	310.0	70573	5.0	.0	****	4.50	.18	1.02	.67	14.00			2	33	36	.04			.02	
310.0	315.0	70574	5.0	.0	****	4.45	.12	.59	.41	10.00			2	33	36	.05			.02	
315.0	320.0	70575	5.0	.0	****	4.81	.22	3.20	4.85	17.00			6	31	37	.05			.12	
320.0	325.0	70576	5.0	.0	****	4.49	.19	2.55	7.10	10.00			6	31	37	.03			.12	
325.0	330.0	70577	5.0	.0	****	4.42	.38	1.87	4.42	7.00			6	31	37	.05			.12	
330.0	335.0	70578	5.0	.0	****	4.27	.16	1.61	2.15	6.00			6	31	37	.12			.12	
335.0	340.0	70579	5.0	.0	****	4.44	.17	3.64	5.67	6.00			7	29	36	.02			.19	
340.0	345.0	70580	5.0	.0	****	4.52	.24	1.42	3.26	4.00			7	29	36	.01			.19	
345.0	350.0	70581	5.0	.0	****	4.60	.27	9.40	15.15	13.00			7	29	36	.02			.19	
350.0	355.0	70582	5.0	.0	****	4.30	.24	.70	2.21	3.00			7	29	36	.03			.19	
355.0	360.0	70583	5.0	.0	****	4.73	.09	4.67	9.63	21.00			6	30	36	.03			.11	
360.0	365.0	70584	5.0	.0	****	4.50	.42	1.20	1.21	21.90						.03				
365.0	370.0	70585	5.0	.0	****	4.50	.24	2.40	3.65	30.20						.03				
370.0	375.0	70586	5.0	.0	****	4.13	.49	.39	1.70	8.00			6	30	36	.03			.11	
375.0	380.0	70587	5.0	.0	****	4.44	.52	.46	1.54	8.00			7	33	40	.02			.12	
380.0	385.0	70588	5.0	.0	****	4.23	.59	.58	1.10	10.00			7	33	40	.02			.12	
385.0	390.0	70589	5.0	.0	****	4.60	.58	.19	1.24	10.00			7	33	40	.05			.12	
390.0	395.0	70590	5.0	.0	****	4.28	.19	.17	1.54	6.00			7	33	40	.64			.12	
395.0	400.0	70591	5.0	.0	****	4.23	.15	1.01	3.03	11.00			6	31	37	.02			.11	
400.0	405.0	70592	5.0	.0	****	4.27	.19	1.20	2.80	5.50						.02				
405.0	410.0	70593	5.0	.0	****	4.30	.25	1.10	2.92	9.00			6	31	37	.02			.11	
410.0	420.0	70594	10.0	.0	****	4.15	.15	2.99	5.43	8.20						.02				
420.0	425.0	70595	5.0	.0	****	4.15		4.40	8.27	21.90						.02				
425.0	430.5	70596	5.5	.0	****	4.15		4.80	5.19	26.00						.02				

DDH: 66030

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													S.G. M.R.
FROM	TO						CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	PY %	TOT Fe	BAO %	Hg %	Mn %	As %	
470.0	475.0	70672	5.0	.0	****	4.85	.09	4.63	9.85	42.80				2	33	35	.02		.01	
475.0	480.0	70673	5.0	.0	****	2.98	.23	.84	4.42	22.70				4	4	8	.15		.06	
480.0	485.0	70674	5.0	.0	****	2.69	.07	.68	.06	15.80				4	4	8	.23		.06	
485.0	490.0	70675	5.0	.0	****	2.74	.06	.38	.01	11.90				4	4	8	.17		.06	
490.0	495.0	70676	5.0	.0	****	2.84	.14	2.06	.01	51.00				4	4	8	.14		.06	
495.0	500.0	70677	5.0	.0	****	2.75	.01	.06	.01	1.70				5	5	10	.16		.03	
500.0	505.0	70678	5.0	.0	****	3.06	.14	.68	2.16	19.70				5	5	10	.15		.03	
505.0	510.0	70679	5.0	.0	****	3.10	.17	1.58	6.42	20.00				5	5	10	.21		.03	
510.0	515.0	70680	5.0	.0	****	3.22	.14	2.93	7.54	34.20				5	5	10	.19		.03	
515.0	520.0	70681	5.0	.0	****	3.21	.06	4.93	9.78	45.30				6	5	11	.21		.02	
520.0	526.0	70682	6.0	.0	****	3.22	.12	1.98	6.13	32.90				6	5	11	.16		.02	

DDH: 66031

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													S.G. W.R.
FROM	TO						CU %	Pb %	Zn %	Ag(AA) g/MT	Ag(FA) g/MT	Au(FA) g/MT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	
385.0	390.0	70687	5.0	.0	****	2.63	.11	.61	1.05	8.00				4	3	8	.17			.06
390.0	395.0	70688	5.0	.0	****	2.70	.11	1.07	.81	14.00				4	3	8	.19			.06
395.0	400.0	70689	5.0	.0	****	2.61	.07	1.68	2.17	13.00				4	3	8	.33			.06
400.0	405.0	70690	5.0	.0	****	3.59	.05	3.12	5.58	30.00				9	20	30	.08			.12
405.0	410.0	70691	5.0	.0	****	4.18	.10	3.35	6.35	43.00				9	20	30	3.37			.12
410.0	416.0	70692	6.0	.0	****	4.19	.13	4.91	6.97	75.00				9	20	30	7.07			.12
416.0	423.0	70693	7.0	.0	****	4.29	.24	5.47	7.80	76.00				9	20	30	3.55			.12
423.0	427.0	70694	4.0	.0	****	4.10	.35	5.90	8.46	86.00				22	11	33	.29			.13
427.0	430.0	70695	3.0	.0	****	4.20	.27	8.63	9.97	100.00				22	11	33	.19			.13
430.0	436.0	70696	6.0	.0	****	3.94	.29	7.49	7.92	76.00				22	11	33	.09			.13
436.0	440.0	70697	4.0	.0	****	3.78	.25	7.10	7.80	66.00				22	11	33	.27			.13
440.0	446.0	70698	6.0	.0	****	4.67	.11	6.57	6.81	80.00				6	29	36	1.31			.22
446.0	450.0	70699	4.0	.0	****	4.44	.18	4.53	7.08	53.00				6	29	36	5.13			.22
450.0	456.0	70700	6.0	.0	****	4.83	.25	5.59	5.83	51.00				6	29	36	.09			.22
456.0	462.0	70701	6.0	.0	****	4.69	.28	5.25	5.98	43.00				5	28	34	.04			.17
462.0	465.0	70702	3.0	.0	****	4.71	.17	6.33	6.97	73.00				5	28	34	4.65			.17
465.0	471.0	70703	6.0	.0	****	4.81	.12	5.75	7.40	60.00				5	28	34	13.94			.17
471.0	476.0	70704	5.0	.0	****	4.70	.06	5.43	8.15	43.00				5	28	34	.18			.17
476.0	482.0	70705	6.0	.0	****	4.43	.28	4.54	6.26	57.00				16	7	24	.13			.04
482.0	490.0	70706	8.0	.0	****	2.71	.06	1.95	2.47	39.00				16	7	24	.15			.04
490.0	492.0	70707	2.0	.0	****	2.61	.01	.78	1.35	17.00				16	7	24	.05			.04

DDH: 66033

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													S.G. W.R.
FROM	TO						CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	
310.0	315.0	70714	5.0	.0	****	3.20	.12	.93	1.22	19.00				11	10	21	.14			.05
315.0	320.0	70715	5.0	.0	****	3.21	.26	.29	.12	5.00				11	10	21	.07			.05
320.0	325.0	70716	5.0	.0	****	3.15	.29	.16	.06	5.00				11	10	21	.08			.05
325.0	330.0	70717	5.0	.0	****	3.35	.26	2.82	4.98	36.50				11	10	21	.16			.05
330.0	335.0	70718	5.0	.0	****	4.16	.33	6.61	9.17	77.00				14	10	25	.08			.14
335.0	340.0	70719	5.0	.0	****	4.04	.31	5.38	8.61	73.00				14	10	25	1.84			.14
340.0	345.0	70720	5.0	.0	****	3.59	.29	3.40	5.69	65.00				14	10	25	1.48			.14
345.0	350.0	70721	5.0	.0	****	2.92	.06	1.93	4.62	33.50				14	10	25	.12			.14
350.0	355.0	70722	5.0	.0	****	3.37	.13	4.51	8.03	57.00				6	19	25	.20			.13
355.0	360.0	70723	5.0	.0	****	5.26	.06	7.05	11.69	74.50				6	19	25	3.30			.13
360.0	365.0	70724	5.0	.0	****	4.51	.22	7.72	6.62	106.00				6	19	25	15.15			.13
365.0	370.0	70725	5.0	.0	****	4.70	.12	5.67	7.58	61.00				6	19	25	17.70			.13
370.0	375.0	70726	5.0	.0	****	4.78	.21	2.94	4.91	31.00				3	30	33	7.18			.08
375.0	380.0	70727	5.0	.0	****	4.71	.07	3.96	6.64	42.00				3	30	33	30.05			.08
380.0	385.0	70728	5.0	.0	****	4.63	.24	4.87	4.12	48.00				3	30	33	4.13			.08
385.0	390.0	70729	5.0	.0	****	4.73	.30	2.58	2.60	37.00				3	30	33	.08			.08
390.0	395.0	70730	5.0	.0	****	4.40	.31	6.75	8.06	48.00				5	30	35	.06			.10
395.0	400.0	70731	5.0	.0	****	4.76	.25	3.67	3.44	42.00				5	30	35	.08			.10
400.0	405.0	70732	5.0	.0	****	4.59	.18	5.11	4.84	52.00				5	30	35	4.75			.10
405.0	410.0	70733	5.0	.0	****	4.57	.18	4.83	5.08	37.00				5	30	35	14.36			.10
410.0	415.0	70734	5.0	.0	****	4.43	.19	1.98	2.25	21.00				3	30	33	2.38			.06
415.0	420.0	70735	5.0	.0	****	4.59	.07	4.67	7.17	52.00				3	30	33	27.16			.06
420.0	425.0	70736	5.0	.0	****	4.36	.19	2.61	3.82	21.00				3	30	33	.13			.06
425.0	430.0	70737	5.0	.0	****	4.75	.25	5.20	11.39	30.00				3	30	33	.03			.06
430.0	435.0	70738	5.0	.0	****	4.48	.58	1.64	1.56	12.00				3	38	41	.12			.06
435.0	440.0	70739	5.0	.0	****	4.61	.33	.89	1.13	8.00				3	38	41	.05			.06
440.0	445.0	70740	5.0	.0	****	5.10	.32	.59	2.07	8.00				3	38	41	.03			.06
445.0	450.0	70741	5.0	.0	****	4.34	.54	1.42	1.88	11.00				3	38	41	.08			.06
450.0	455.0	70742	5.0	.0	****	4.58	.33	1.65	3.05	9.00				3	36	39	.02			.05
455.0	461.5	70743	6.5	.0	****	4.69	.14	3.51	6.33	17.00				3	36	39	.02			.05

DDH: 66057

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														S.G. W.R.
FROM	TO						CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %	
295.0	300.0	70957	5.0	.0	****	3.81	.03	.91	3.49	21.90				7	11	19	.10			.06	
300.0	305.0	70958	5.0	.0	****	3.81	.08	1.50	4.23	16.30				7	11	19	.10			.06	
305.0	310.0	70959	5.0	.0	****	3.32	.32	3.06	4.02	40.10				7	11	19	.08			.06	
360.0	365.0	70961	5.0	.0	****	2.77	.18	1.30	.16	34.00				3	18	21	.13			.04	
365.0	370.0	70962	5.0	.0	****	3.45	.33	2.21	.62	40.40				3	18	21	.09			.04	
370.0	375.0	70963	5.0	.0	****	3.04	.06	.76	.50	9.00				3	18	21	.04			.04	
375.0	380.0	70964	5.0	.0	****	3.20	.03	.50	1.68	20.00				3	18	21	.15			.04	
380.0	385.0	70965	5.0	.0	****	3.23	.11	1.54	3.45	16.20				4	7	11	.15			.05	
385.0	390.0	70966	5.0	.0	****	3.12	.10	1.68	4.37	22.20				4	7	11	.17			.05	
390.0	395.0	70967	5.0	.0	****	2.66	.14	1.06	.36	24.00				4	7	11	.10			.05	
395.0	400.0	70968	5.0	.0	****	3.19	.25	1.14	2.48	19.30				4	7	11	.11			.05	
400.0	405.0	70969	5.0	.0	****	3.26	.23	1.88	4.62	24.30				5	11	16	.06			.05	
405.0	410.0	70970	5.0	.0	****	3.47	.06	3.62	11.03	27.00				3	12	16	.14			.04	
410.0	415.0	70971	5.0	.0	****	3.35	.16	.66	2.96	12.20				3	12	16	.14			.04	
415.0	420.0	70972	5.0	.0	****	3.57	.08	2.96	7.80	25.70				3	12	16	.11			.04	
420.0	425.0	70973	5.0	.0	****	3.64	.04	5.10	14.30	34.00				4	9	13	.12			.04	
425.0	430.0	70974	5.0	.0	****	2.89	.23	1.98	3.54	19.70				4	9	13	.13			.04	
430.0	435.0	70975	5.0	.0	****	3.48	.12	5.79	9.02	43.20				4	9	13	.12			.04	
435.0	440.0	70976	5.0	.0	****	3.19	.16	3.52	7.93	23.30				4	9	13	.11			.04	
440.0	445.0	70977	5.0	.0	****	3.33	.07	2.36	6.47	32.90				3	10	14	.11			.03	
445.0	450.0	70978	5.0	.0	****	3.40	.06	4.92	12.00	28.20				3	10	14	.10			.03	
450.0	455.0	70979	5.0	.0	****	3.28	.14	3.52	7.38	28.60				3	10	14	.09			.03	
455.0	460.0	70980	5.0	.0	****	3.47	.07	3.86	9.41	39.90				3	10	14	.11			.03	
460.0	465.0	70981	5.0	.0	****	3.45	.11	1.80	5.08	27.20				5	10	15	.23			.03	
465.0	470.0	70982	5.0	.0	****	3.31	.17	1.90	4.15	28.60				5	10	15	.10			.03	

DDH: 66E-01

					-----ASSAYS-----															
DEPTHS	SAMPLE	INT.	REC.	ROCK	S.G.	CU	Pb	Zn	Ag(AA)	Ag(FA)	Au(FA)	Po	Py	TOT	BAO	Hg	Mn	As	Ba	S.G.
FROM	TO	NO.		UNIT	PULP	%	%	%	g/mT	g/mT	g/mT	%	%	Fe	%	%	%	%	%	W.R.
150.0	155.0	70988	5.0	.0	2C3	3.05	<i>23</i> .14	.10	.16	5.90				7	13	20	.30			.08
155.0	160.0	70989	5.0	.0	2C3	3.32	.29	.52	.14	16.90				7	13	20	.05			.08
160.0	165.0	70990	5.0	.0	2D0	3.74	.10	3.25	6.53	60.70			.14	7	13	20	.32			.08
165.0	170.0	70991	5.0	.0	2D0	3.41	.12	3.13	5.91	53.30			.01	6	11	18	1.76			.17
170.0	175.0	70992	5.0	.0	2D0	2.92	<i>23</i> .04	2.94	3.57	47.40			.01	6	11	18	.40			.17
175.0	180.0	70993	5.0	.0	2B0	3.17	.12	1.68	2.92	32.70			.01	6	11	18	.28			.17
180.0	185.0	70994	5.0	.0	2F4	4.45	<i>50</i> .14	6.06	10.10	49.10			.01	6	11	18	.08			.17
185.0	190.0	70995	5.0	.0	2F4	4.93	.06	5.00	9.06	41.50			1.58	10	25	36	.02			.11
190.0	195.0	70996	5.0	.0	2H4	4.31	<i>70</i> .27	4.44	8.85	45.30			.14	10	25	36	.06			.11
195.0	200.0	70997	5.0	.0	2H34	4.28	.19	2.21	5.97	22.00			.06	10	25	36	.12			.11

DDH: 66E-04

---DEPTHS---		SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	---ASSAYS---					S.G. W.R.
FROM	TO											Po %	Py %	TOT Fe %	BAO %	Hg %	
130.0	135.0	71003	5.0	.0	2D4	3.28	18	7.49	5.17	133.80	.06	6	16	23	.77	.20	
135.0	140.0	71004	5.0	.0	2C2	3.06	11	.36	.12	6.80	.01	6	16	23	.38	.20	
140.0	145.0	71005	5.0	.0	2F4	4.04	14	7.88	6.40	112.50	.14	6	16	23	1.95	.20	
145.0	150.0	71006	5.0	.0	2D0	3.37	14	5.49	3.95	69.40	.01	6	16	23	.32	.20	
150.0	155.0	71007	5.0	.0	2F4	5.34	.12	4.23	6.10	31.30	.07	6	16	23	.02	.20	
155.0	160.0	71008	5.0	.0	2F4	4.84	04	4.87	9.96	48.80	.07	7	26	33	.02	.07	
160.0	165.0	71009	5.0	.0	2F4	4.85	05	6.30	11.33	74.80	.07	7	26	33	.02	.07	
165.0	170.0	71010	5.0	.0	2F4	4.96	.21	4.41	7.63	54.20	.01	7	26	33	.23	.07	
170.0	175.0	71011	5.0	.0	2D0	3.57	.21	2.96	5.06	42.60	.01	7	26	33	.52	.07	
175.0	180.0	71012	5.0	.0	2D0	3.43	.14	1.95	3.42	30.50	.01	11	10	22	1.04	.06	
180.0	185.0	71013	5.0	.0	2C0	3.37	23	1.28	2.51	19.90	.01	11	10	22	.44	.06	
185.0	190.0	71014	5.0	.0	2H4	3.87	.25	4.18	8.17	71.40	.07	11	10	22	1.63	.06	
190.0	195.0	71015	5.0	.0	2CH	3.11	10	2.21	3.62	41.50	.01	11	10	22	.55	.06	
195.0	200.0	71016	5.0	.0	2D1	3.22	.09	1.76	2.88	31.30	.14	3	12	15	.52	.06	
200.0	205.0	71017	5.0	.0	2C1	3.10	.06	.37	.69	9.80		3	12	15	.81	.06	
205.0	210.0	71018	5.0	.0	2C1	3.08	10	.19	1.64	8.00		3	12	15	.54	.06	
210.0	215.0	71019	5.0	.0	2D1	3.25	.10	1.73	4.08	41.30	.21	3	12	15	.67	.06	
215.0	220.0	71020	5.0	.0	2A54	3.26	.09	3.77	4.67	66.20	.21	4	5	10	.68	.04	
220.0	225.0	71021	5.0	.0	2A51	3.21	11	.98	1.90	30.50	.27	4	5	10	.68	.04	
225.0	230.0	71022	5.0	.0	2A5	2.61		.83	1.32	16.90		4	5	10	.95	.04	
230.0	235.0	71023	5.0	.0	2A5	2.56		.46	.55	6.30		4	5	10	.86	.04	
235.0	240.0	71024	5.0	.0	2A5	2.69		.50	1.30	8.00		5	3	9	.54	.04	
240.0	245.0	71025	5.0	.0	2A5	2.61	.05	.52	1.59	9.40		5	3	9	.37	.04	
245.0	250.0	71026	5.0	.0	2A5	2.93	.31		.32	14.30		5	3	9	.25	.04	

650'
0.15, 4.12, 5.65, 56.23

DDH: 66E-05 Suspect collar coords

---DEPTHS---				-----ASSAYS-----																
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
240.0	245.0	71033	5.0	.0	1D14 ****	3.02		.01	5.50					5 18 23	.33					.09
245.0	250.0	71034	5.0	.0	2C8	3.15	.10	.88	1.91	15.30				5 18 23	.38					.09
250.0	255.0	71035	5.0	.0	2CA	3.02		.81	1.20	13.60				5 18 23	.94					.09
255.0	260.0	71036	5.0	.0	2E14	3.38	.24	2.25	4.18	32.20			.07	5 18 23	.35					.09
260.0	265.0	71037	5.0	.0	2E80	3.59	.61	1.30	1.92	23.20			.01	5 18 23	.05					.09
265.0	270.0	71038	5.0	.0	2E80	4.72	.20	2.01	1.36	25.30			.01	5 36 41	.06					.15
270.0	275.0	71039	5.0	.0	2E84	4.76	.07	1.72	3.03	20.70			.01	5 36 41	.03					.15
275.0	280.0	71040	5.0	.0	2E84	4.67	.05	2.25	3.60	21.20			.01	5 36 41	.02					.15
280.0	285.0	71041	5.0	.0	2E84	4.78		2.77	5.18	25.30			.07	5 36 41	.02					.15
285.0	290.0	71042	5.0	.0	2E4	4.10	.39	2.27	4.73	31.50			.07	30 14 44	.14					.05
290.0	295.0	71043	5.0	.0	2H4	4.08	.73	2.01	3.62	37.60			.07	30 14 44	.07					.05
295.0	300.0	71044	5.0	.0	2H0	3.90	.57	.97	2.41	34.10			.07	30 14 44	.05					.05
300.0	305.0	71045	5.0	.0	2H0	3.92	.49	1.43	2.55	47.30			.07	30 14 44	.06					.05
305.0	310.0	71046	5.0	.0	2C0	2.90	.16	.41	2.35	13.00			.01	7 7 15	.27					.11
310.0	315.0	71047	5.0	.0	2D0	2.88	.13	1.82	4.48	30.60			.07	7 7 15	.20					.11
315.0	320.0	71048	5.0	.0	2D4	3.34	.24	7.86	12.25	116.80			.01	7 7 15	.18					.11
320.0	325.0	71049	5.0	.0	2D0	3.05	.07	2.14	4.27	70.10				7 7 15	.49					.11
325.0	330.0	71050	5.0	.0	2A0	2.61	.02	.83	1.50	17.50				2 1 3	.88					.03
330.0	335.0	71051	5.0	.0	2A0	2.69	.03	.87	1.23	18.50				2 1 3	.62					.03
335.0	340.0	71052	5.0	.0	2A0	2.54	.01	.54	1.54	11.40				2 1 3	.77					.03
340.0	345.0	71053	5.0	.0	2A0	2.69	.03	.78	1.82	22.20				2 1 3	.35					.03

hole located in wrong place

0.15 3.99 7.00 7.25

DDH: 66E-06

---DEPTHS---		SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	---ASSAYS---					Hg %	Mn %	As %	Ba %	S.G. W.R.
FROM	TO											Po %	Py %	TOT Fe	BAO %						
205.0	210.0	71057	5.0	.0 2A4	3.52	.09	1.93	3.38	8.00			2	21	24	.03						.04
210.0	215.0	71058	5.0	.0 2C0	3.45	.07	.47	2.86	4.50			2	21	24	.04						.04
215.0	220.0	71059	5.0	.0 2D0	3.59	<i>23</i> .03	1.76	5.85	14.60			2	21	24	.11						.04
220.0	225.0	71060	5.0	.0 2D0	3.28	.09	4.07	4.44	56.70			8	9	18	7.01						.40
225.0	230.0	71061	5.0	.0 2D4	3.99	.13	10.35	8.13	137.90			8	9	18	1.64						.40
230.0	235.0	71062	5.0	.0 2D0	2.98	<i>23</i> .04	2.44	2.26	31.50			8	9	18	2.45						.40
235.0	240.0	71063	5.0	.0 2E0	3.37	.07	3.76	2.22	52.00			8	9	18	5.59						.40
240.0	245.0	71064	5.0	.0 1D4/9	2.99	<i>Wash</i> .06	1.25	1.22	21.70	.01		8	15	24	4.48						.13
245.0	250.0	71065	5.0	.0 1D4	2.75	.04	.66	.95	17.60	.06		8	15	24	2.34						.13
250.0	255.0	71066	5.0	.0 2J3	4.31	.31	2.94	5.90	38.30			8	15	24	.50						.13
255.0	260.0	71067	5.0	.0 2J3	4.31	<i>50</i> .24	2.41	5.05	33.60			8	15	24	.04						.13
260.0	265.0	71068	5.0	.0 2J3	4.33	.36	2.58	4.35	31.90			6	25	32	.04						.07
265.0	275.0	71069	10.0	.0 2F0	4.82	<i>50</i> .12	2.97	6.01	18.50			6	25	32	.02						.07
275.0	280.0	71070	5.0	.0 2D0	2.95	.04	2.10	4.03	20.30	.06		6	25	32	.54						.07
280.0	285.0	71071	5.0	.0 2D0	2.86	.02	2.48	5.33	27.70	.06		5	9	15	.59						.04
285.0	290.0	71072	5.0	.0 2D0	3.53	<i>21</i> .21	3.90	5.04	51.00	.20		5	9	15	.13						.04
290.0	295.0	71073	5.0	.0 2D0	2.95	.02	1.07	4.46	22.10	.14		5	9	15	.43						.04
295.0	300.0	71074	5.0	.0 2D0	2.94	.03	1.42	4.64	26.50	.14		5	9	15	.31						.04
300.0	305.0	71075	5.0	.0 2A4	2.78	<i>21</i> .02	1.30	2.77	25.90	.34		3	2	6	.21						.02
305.0	311.0	71076	6.0	.0 2D0	3.05	.07	1.92	3.72	34.70	.34		3	2	5	.13						.01

DDH: 66E-07

---DEPTHS---				-----ASSAYS-----																
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
215.0	220.0	71082	5.0	.0 2B0	2.90	.06	.22	.20	10.40			3	3	7	.49					.04
220.0	225.0	71083	5.0	.0 2D4	3.03 ²³	.07	3.62	7.28	60.30			.07	3	3	7	.11				.04
225.0	230.0	71084	5.0	.0 2C5	2.85	.05	2.65	1.66	37.00			.07	3	3	7	.18				.04
230.0	231.6	71085	1.6	.0 2A4	2.97 ²¹	.04	1.86	3.17	30.20			.07	6	5	11	.45				.14
231.6	236.0	71086	4.4	.0 2C0	2.83	.03	.76	1.48	12.30			.07	6	5	11	.38				.14
236.0	241.0	71087	5.0	.0 2A4	3.08	.03	1.55	3.35	29.00			.14	6	5	11	.39				.14
241.0	245.0	71088	4.0	.0 2D4	3.98 ²¹	.12	5.52	11.38	97.70 ⁹⁰			.07	6	5	11	.07				.14
245.0	250.0	71089	5.0	.0 2D4	3.02	.06	10.62	14.65	197.50			.14	6	5	11	.17				.14

DDH: 66E-09

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	---ASSAYS---				S.G. W.R.			
FROM	TO												Po %	Py %	TOT Fe	BAO %		Hg %	Mn %	As %
230.0	234.0	71101	4.0	.0	2CE	3.13	.28	.27	6.30				3	17	20	.17				.05
234.0	240.0	71102	6.0	.0	2D4	3.97	23.03	5.73	11.14	33.60		1.37	3	17	20	.11				.05
285.0	290.0	71104	5.0	.0	2E0	3.08	.25	.87	.21	23.10			10	25	36	.30				.18
290.0	295.0	71105	5.0	.0	2E0	4.04	40.25	.01		5.00			10	25	36	.03				.18
295.0	300.0	71106	5.0	.0	2E0	3.46	1.03	.87	.65	39.00			10	25	36	.05				.18
300.0	310.0	71107	10.0	.0	1D/2E	3.76	40.42	3.97	2.11	87.00		1.78	10	25	36	3.09				.18
310.0	315.0	71108	5.0	.0	2E4	3.57	20	2.39	1.95	35.80		.34	7	32	40	.05				.33
315.0	320.0	71109	5.0	.0	2E84	4.63	.24	2.48	2.37	27.30		.82	7	32	40	.03				.33
320.0	325.0	71110	5.0	.0	2E84	4.95	40.27	3.46	2.22	38.30		.41	7	32	40	.02				.33
325.0	330.0	71111	5.0	.0	2E1	3.41	40.27	1.15	.69	13.40		.27	7	32	40	.08				.33
330.0	335.0	71112	5.0	.0	2B0	4.80	.23	.45		8.10		.14	2	39	41	.06				.06
335.0	340.0	71113	5.0	.0	2E4	4.81	.19	2.52	2.65	22.90		.07	2	39	41	.04				.06
340.0	345.0	71114	5.0	.0	2E0	4.76	26	1.18	.78	22.80		.07	2	39	41	.04				.06
345.0	350.0	71115	5.0	.0	2E4	4.83	50.15	3.08	4.28	28.70		.07	2	39	41	.03				.06
350.0	355.0	71116	5.0	.0	2E4	4.32	.18	2.95	5.39	29.10		.07	1	32	34	.03				.06
355.0	360.0	71117	5.0	.0	2CE	3.80	.08	1.91	.39	27.40			1	32	34	.02				.06
360.0	365.0	71118	5.0	.0	2E0	4.39	.10	1.08	.71	12.50			1	32	34	.02				.06
365.0	370.0	71119	5.0	.0	2E0	3.91	40.14	.52	.50	11.20			1	32	34	.02				.06
370.0	375.0	71120	5.0	.0	2C0	3.17	.08	.78	2.42	9.90		.21	1	26	27	.15				.02
375.0	380.0	71121	5.0	.0	2F4	4.09	.05	5.41	8.10	38.10		.14	1	26	27	.08				.02
380.0	385.0	71122	5.0	.0	2CE	3.91	.21	1.54	2.11	17.60		.07	1	26	27	.08				.02
385.0	390.0	71123	5.0	.0	2CE4	4.23	40.20	2.08	3.17	19.00		.07	1	26	27	.11				.02
390.0	395.0	71124	5.0	.0	2CE	4.01	.42	.62	1.00	9.00		.07	5	28	34	.02				.21
395.0	400.0	71125	5.0	.0	2C0	4.20	.43	.39	1.00	9.10		1.10	5	28	34	.04				.21
400.0	405.0	71126	5.0	.0	2D0	4.36	.36	1.87	2.32	13.60		.07	5	28	34	.01				.21
405.0	410.0	71127	5.0	.0	2D0	3.86	40.25	3.04	3.46	17.90			5	28	34	.03				.21
410.0	415.0	71128	5.0	.0	2E8	4.12	.27	1.13	1.81	9.30		.01	4	25	30	.03				.19
415.0	420.0	71129	5.0	.0	2CE4	3.71	.19	2.20	4.07	13.10			4	25	30	.04				.19
420.0	425.0	71130	5.0	.0	2CE4	3.43	.08	.57	5.07	6.60			4	25	30	.15				.19
425.0	430.0	71131	5.0	.0	2CE	4.15	21.30	.41	1.73	7.50			4	25	30	.04				.19
430.0	435.0	71132	5.0	.0	2CE4	3.79	.14	1.34	3.48	8.00		.03	3	24	27	.03				.07
435.0	440.0	71133	5.0	.0	2EC4	3.81	21.06	3.49	8.02	18.50		.03	3	24	27	.11				.07
440.0	446.5	71134	6.5	.0	2EC4	4.16	.09	4.17	10.35	15.80		.03	3	24	27	.04				.07

Waste

DDH: 67-02

					-----ASSAYS-----																
---DEPTHS---	SAMPLE	INT.	REC.	ROCK	S.G.	CU	Pb	Zn	Ag(AA)	Ag(FA)	Au(FA)	Po	Py	TOT	BAO	Hg	Mn	As	Ba	S.G.	
FROM	TO	NO.		UNIT	PULP	%	%	%	g/mT	g/mT	g/mT	%	%	Fe	%	%	%	%	%	W.R.	
438.5	444.0	71146	5.5	2DE	2.79	.09	1.79	2.94	13.10		.07	4	19	23	.04						.05
444.0	448.5	71147	4.5	2DE <i>to</i>	3.30	.11	3.37	10.02	20.20		.14	4	19	23	.09						.05

DDH: 67-03

-----DEPTHS-----				-----ASSAYS-----																
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
439.0	444.0	71156	5.0	.0 2C0	2.93	.07	1.64	.11	32.90				5	7	12	.68				.16
444.0	449.0	71157	5.0	.0 2D4	3.41	.10	4.33	6.28	48.90			.27	5	7	12	.24				.16
449.0	454.0	71158	5.0	.0 2B4	3.90	.20	3.25	8.38	41.40			.62	4	19	24	.23				.17
454.0	459.0	71159	5.0	.0 2EG	4.65	.04	4.94	6.66	66.60		2.54	4	19	24	16.04					.17
459.0	464.0	71160	5.0	.0 2G4	4.62	.14	8.08	7.00	115.40		.01	4	19	24	21.96					.17
464.0	469.0	71161	5.0	.0 2G/1D	3.83	.03	2.83	4.68	46.00		.07	4	19	24	26.51					.17
509.0	514.0	71164	5.0	.0 2B0	3.14	.05	2.09	2.26	31.20		.07	14	13	28	7.05					.21
514.0	519.0	71165	5.0	.0 2B4	4.03	.16	5.00	6.45	79.40		.07	14	13	28	2.97					.21
519.0	524.0	71166	5.0	.0 2D4	3.97	.20	4.50	7.05	67.40		.01	14	13	28	.64					.21
524.0	529.0	71167	5.0	.0 2H4	4.34	.25	6.18	9.90	68.50		.01	14	13	28	.07					.21
529.0	534.0	71168	5.0	.0 2E4	4.34	.25	5.20	9.88	53.20		.07	17	23	40	.03					.22
534.0	539.0	71169	5.0	.0 2H8	4.53	.12	2.29	1.52	36.20		.01	17	23	40	.04					.22
539.0	544.0	71170	5.0	.0 2H8	4.36	.27	1.07	1.02	16.30		.01	17	23	40	.04					.22
544.0	549.0	71171	5.0	.0 2E0	4.59	.13	1.66	1.61	16.60		.01	17	23	40	.03					.22
549.0	554.0	71172	5.0	.0 2E4	4.55	.07	5.49	9.65	52.30		.07	8	22	31	.02					.09
554.0	559.0	71173	5.0	.0 2EH	4.74	.21	5.70	9.84	38.20		.07	8	22	31	.02					.09
559.0	564.0	71174	5.0	.0 2HF	4.90	.12	5.06	9.59	34.70		.07	8	22	31	.03					.09
564.0	569.0	71175	5.0	.0 2C0	3.34	.13	.72	1.36	9.80		.07	8	22	31	.25					.09
569.0	574.0	71176	5.0	.0 2C0	3.61	.05	1.09	1.02	60.70		.62	3	23	27	.25					.14
574.0	579.0	71177	5.0	.0 2D0	3.54	.03	1.11	3.79	17.20		.27	3	23	27	.27					.14
579.0	584.0	71178	5.0	.0 2F4	4.18	.24	5.45	10.90	40.60		.01	3	23	27	.04					.14
584.0	589.0	71179	5.0	.0 2F0	4.12	.13	2.33	7.56	33.40		.07	3	23	27	.04					.14
589.0	594.0	71180	5.0	.0 2D0	3.46	.21	2.32	4.46	25.40		.07	11	11	22	.28					.08
594.0	599.0	71181	5.0	.0 2ED	3.07	.14	3.18	6.11	25.00		.14	11	11	22	.31					.08
599.0	604.0	71182	5.0	.0 2H4	3.69	.10	1.71	6.31	38.90		.07	11	11	22	.06					.08
604.0	609.0	71183	5.0	.0 2A4	3.54	.06	1.19	4.63	28.10		.07	11	11	22	.27					.08
609.0	614.0	71184	5.0	.0 2A4	3.05	.08	1.24	2.88	18.80		.07	4	5	10	.16					.03
614.0	619.0	71185	5.0	.0 2A4	2.84	.04	1.45	4.95	22.70		.01	4	5	10	.21					.03
619.0	624.0	71186	5.0	.0 2A0	2.77	.08	.72	2.78	21.80		.07	4	5	10	.20					.03
624.0	629.0	71187	5.0	.0 2A0	2.92	.09	1.10	1.75	18.10			4	5	10	.17					.03

DDH: 67-05

---DEPTHS---		SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	---ASSAYS---							S.G. W.R.	
FROM	TO											Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %		Ba %
308.0	313.0	71249	5.0	.0 2DE	3.44	.09	3.58	4.67	56.10		.07	12	12	25	1.60					.09
313.0	318.0	71250	5.0	.0 2DE4	4.07	33.21	3.66	7.95	57.60		.07	12	12	25	.62					.09
360.0	365.0	71252	5.0	.0 2D6	3.29	.09	1.84	2.63	31.50		.01	30	7	38	10.66					.06
365.0	370.0	71253	5.0	.0 2H4	4.51	70.21	7.13	11.30	74.30			30	7	38	.15					.06
370.0	375.0	71254	5.0	.0 2H4	4.59	70.18	7.00	14.00	68.10		.07	30	7	38	.02					.06
375.0	380.0	71255	5.0	.0 2H4	4.22	.22	2.20	5.86	30.60		.07	30	7	38	.05					.06
380.0	385.0	71256	5.0	.0 2C0	3.42	.16	.61	.76	17.10			22	8	31	.02					.05
385.0	390.0	71257	5.0	.0 2C0	3.35	70.14	.55	.62	10.50			22	8	31	.07					.05
390.0	395.0	71258	5.0	.0 2DH	3.81	70.19	1.82	3.93	24.50		.07	22	8	31	.11					.05
395.0	400.0	71259	5.0	.0 2D7	3.63	.45	1.40	3.27	21.00		.41	22	8	31	.23					.05
400.0	405.0	71260	5.0	.0 2H4	4.11	.28	1.86	3.86	23.40		.27	30	12	43	.09					.17
405.0	410.0	71261	5.0	.0 2H4	4.10	70.26	1.53	3.52	30.00		.01	30	12	43	.02					.17
410.0	415.0	71262	5.0	.0 2HE4	4.39	.26	4.59	10.20	40.90		.01	30	12	43	.15					.17
415.0	420.0	71263	5.0	.0 2F4	4.42	.13	4.50	8.15	41.50		.07	30	12	43	.03					.17
420.0	425.0	71264	5.0	.0 2F4	4.29	50.16	5.21	9.17	38.50			5	30	35	.03					.17
425.0	430.0	71265	5.0	.0 2FE	4.44	.16	3.68	5.58	26.10		.07	5	30	35	.05					.17
430.0	435.0	71266	5.0	.0 2E84	3.90	.11	.94	2.13	8.40		.01	5	30	35	.03					.17
435.0	440.0	71267	5.0	.0 2F0	3.27	70.08	1.89	4.93	8.60		.07	5	30	35	.05					.17
440.0	445.0	71268	5.0	.0 2H4	2.85	70.24	2.46	5.74	10.80		.01	13	10	23	.04					.06
445.0	450.0	71269	5.0	.0 2D0	3.79	.27	2.96	5.76	22.40		.07	13	10	23	.11					.06
450.0	455.0	71270	5.0	.0 2A4	3.15	21.07	2.68	7.89	36.40		.14	13	10	23	.26					.06
455.0	460.0	71271	5.0	.0 2D0	3.02	.06	1.59	4.54	26.20		.01	13	10	23	.39					.06
460.0	465.0	71272	5.0	.0 2C0	3.09	.21	1.04	2.18	16.30			8	11	20	.34					.06
465.0	470.0	71273	5.0	.0 2EA	3.36	21.14	2.35	4.82	32.50		.07	8	11	20	.22					.06
470.0	475.0	71274	5.0	.0 2DE	3.50	.23	2.77	4.80	44.10		.07	8	11	20	.13					.06
475.0	480.0	71275	5.0	.0 2DE	3.33	.12	1.47	3.04	28.50		.14	8	11	20	.13					.06
480.0	485.0	71276	5.0	.0 2A4	3.02	21.09	1.38	3.95	29.60		.14	4	3	7	.18					.04
485.0	490.0	71277	5.0	.0 2A0	2.75	.08	.98	1.30	23.70			4	3	7	.24					.04

Waste

DDH: 67-07

-----DEPTHS-----		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													S.G. W.R.
FROM	TO						CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	
366.0	371.0	71338	5.0	.0	2DA	3.13	.16	1.58	3.25	29.00		.07	6	4	10	.25		.08		
371.0	376.0	71339	5.0	.0	2DA 21	2.94	.13	2.86	3.56	53.40		.07	6	4	10	.32		.08		
376.0	381.0	71340	5.0	.0	2DA	2.78	.05	3.36	1.29	73.20		.07	6	4	10	.30		.08		

DDH: 67-08

-----DEPTHS-----					-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
630.0	635.0	71351	5.0	.0 2C7	3.54	.31	.07	.43	9.90					8	9	18				.02
635.0	640.0	71352	5.0	.0 2C7	3.81	40.37	.55	1.15	14.20					3	23	26				.04
640.0	645.0	71353	5.0	.0 2CE	3.72	.21	.54	2.50	6.60					3	23	26				.04
645.0	650.0	71354	5.0	.0 2CE	3.87	.14	.80	1.22	5.60					3	23	26				.04
650.0	655.0	71355	5.0	.0 2D3	4.23	40.01	1.99	3.04	6.60		.07			3	23	26				.04
655.0	660.0	71356	5.0	.0 2C3	3.75	.16	.48	1.52	5.10		.07			4	17	22				.03
660.0	665.0	71357	5.0	.0 2D3	3.67	.11	2.01	4.93	13.20		.07			4	17	22				.03
665.0	670.0	71358	5.0	.0 2D43	3.62	.04	4.29	12.25	17.20		.07			4	17	22				.03
670.0	675.0	71359	5.0	.0 2D43	3.65	21.11	5.20	15.50	26.70		.07			4	17	22				.03
675.0	680.0	71360	5.0	.0 2D0	3.08	.13	1.47	2.59	20.20		.14			4	3	8				.05
680.0	685.0	71361	5.0	.0 2B4	3.05	.06	8.74	5.11	109.20		.96			4	3	8				.05
685.0	690.0	71362	5.0	.0 2B4	2.89	21.07	2.37	3.27	48.70		.14			4	3	8				.05
690.0	695.0	71363	5.0	.0 2B/1D	2.94	.02	1.38	4.78	32.50		.07			4	3	8				.05

DDH: 67-09

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													S.G. W.R.
FROM	TO						CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	
655.0	660.0	71374	5.0	.0	2C0	3.33	.07	1.23	2.25	10.40			.01	3	22	26	.24		.13	
660.0	665.0	71375	5.0	.0	2CE	4.02	.27	.04	.88	12.30				3	22	26	.05		.13	
665.0	670.0	71376	5.0	.0	2CE	3.87	.47	.05	.50	9.20				3	22	26	.02		.13	
670.0	675.0	71377	5.0	.0	2CE	4.16	.47	.20	1.81	9.70				3	22	26	.01		.13	
675.0	680.0	71378	5.0	.0	2CE	4.18	.20	1.83	1.91	6.80			.01	7	26	33	.01		.15	
680.0	685.0	71379	5.0	.0	2E0	4.35	.25	.60	1.49	8.30				7	26	33	.02		.15	
685.0	690.0	71380	5.0	.0	2E0	4.20	.22	.83	2.49	6.30			.01	7	26	33	.02		.15	
690.0	695.0	71381	5.0	.0	2D7	3.91	.25	1.30	3.84	16.10			.01	7	26	33	.03		.15	
695.0	700.0	71382	5.0	.0	2B4	3.29	.08	4.23	9.38	38.50			.14	3	4	8	.21		.06	
700.0	705.0	71383	5.0	.0	2B4	2.86	.07	1.90	4.01	31.70				3	4	8	.44		.06	
705.0	710.0	71384	5.0	.0	2B4	2.88	.10	1.40	3.40	30.20				3	4	8	.59		.06	
710.0	715.0	71385	5.0	.0	2B4	2.83	.09	1.55	3.09	30.60				3	4	8	.68		.06	
715.0	720.0	71386	5.0	.0	2B4	2.89	.14	1.60	2.83	31.40			.01	3	3	6	.36		.07	
720.0	725.0	71387	5.0	.0	2B0	2.84	.09	.66	1.34	18.60				3	3	6	.23		.07	

DDH: 67-10

DEPTHS				INT. REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	ASSAYS									
FROM	TO	SAMPLE NO.	Po %										Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %	S.G. W.R.		
404.0	409.0	71394	5.0	.0	2C5	3.24	.17	.18	.65	6.10			5	14	19	.13						.04
409.0	414.0	71395	5.0	.0	2C5	3.45	.10	.20	.61	6.90			5	14	19	.06						.04
414.0	419.0	71396	5.0	.0	2C5	3.25	.14	.25	.44	7.10			3	16	19	.09						.05
419.0	424.0	71397	5.0	.0	2C5	3.43	.07	.23	1.02	5.10			3	16	19	.05						.05
424.0	429.0	71398	5.0	.0	2C0	3.35	.08	.14	1.31	5.90			3	16	19	.05						.05
429.0	434.0	71399	5.0	.0	2C5	3.12	.17	.10	.81	5.90			3	16	19	.14						.05
434.0	439.0	71400	5.0	.0	2C5	3.07	.24	3.06	.33	102.80	14.90		3	4	7	.25						.07
479.0	484.0	71402	5.0	.0	2C0	3.24	.12	2.09	.80	33.90	.14		8	12	21	1.28						.10
484.0	489.0	71403	5.0	.0	2C0	3.42	.14	2.42	1.66	44.50			8	12	21	2.35						.10
489.0	494.0	71404	5.0	.0	2H4	3.52	.25	6.77	3.98	133.50			5	26	31	2.48						.11
494.0	499.0	71405	5.0	.0	1D4/9	4.06	.23	1.51	1.06	28.90	.27		5	26	31	.20						.11
499.0	506.5	71406	7.5	.0	2E0	4.26	.11	.98	.96	12.30			5	26	31	.09						.11
506.5	514.0	71407	7.5	.0	2CE	4.29	.04	.78	.36	9.50			5	26	31	.07						.11
514.0	519.0	71408	5.0	.0	2CE	4.52	.15	.50	.50	9.00			2	30	32	.02						.02
519.0	524.0	71409	5.0	.0	2C0	4.24	.02	.24	.14	5.90			2	30	32	.02						.02
524.0	529.0	71410	5.0	.0	2C0	3.29	.08	.67	.04	31.00			2	30	32	.03						.02
529.0	534.0	71411	5.0	.0	2C0	3.71	.02	1.17	.32	23.90			2	30	32	.04						.02
534.0	539.0	71412	5.0	.0	2CF	4.05	.35	2.86	4.30	37.20	.14		5	33	39	.02						.15
539.0	544.0	71413	5.0	.0	2CE	4.28	.09	1.04	.96	13.50	.41		5	33	39	.03						.15
544.0	549.0	71414	5.0	.0	2E4	4.37	.20	1.76	2.69	24.80	.01		5	33	39	.03						.15
549.0	554.0	71415	5.0	.0	2E4	4.50	.26	2.79	3.64	31.30	.01		5	33	39	.02						.15
554.0	559.0	71416	5.0	.0	2E0	4.42	.08	1.30	1.24	18.10	.07		1	36	38	.02						.04
559.0	564.0	71417	5.0	.0	2E4	4.80	.11	4.63	3.60	41.40	.01		1	36	38	.02						.04
564.0	569.0	71418	5.0	.0	1D4	4.53	.08	1.10	1.75	18.30	.21		1	36	38	.05						.04
569.0	574.0	71419	5.0	.0	2D0	4.28	.17	2.63	2.60	23.00	.01		1	36	38	.07						.04
574.0	579.0	71420	5.0	.0	2C0	4.18	.39	.60	1.11	9.70	.07		5	30	35	.02						.21
579.0	584.0	71421	5.0	.0	2CF	4.10	.11	3.26	6.70	25.00	.14		5	30	35	.09						.21
584.0	589.0	71422	5.0	.0	2E84	4.66	.41	1.50	2.66	18.30	.07		5	30	35	.02						.21
589.0	594.0	71423	5.0	.0	2E84	4.07	.25	1.32	2.88	11.00	.01		5	30	35	.02						.21
594.0	599.0	71424	5.0	.0	2E84	4.33	.28	2.33	3.85	13.40	.01		4	30	34	.03						.14
599.0	604.0	71425	5.0	.0	2C0	3.85	.15	.18	.58	5.30	.14		4	30	34	.07						.14
604.0	609.0	71426	5.0	.0	2D0	4.29	.25	1.60	4.61	9.20	.01		4	30	34	.04						.14
609.0	614.0	71427	5.0	.0	2F4	4.83	.03	6.07	10.94	27.20	.07		4	30	34	.02						.14
614.0	619.0	71428	5.0	.0	2E4	4.21	.10	3.95	8.04	19.40	.07		4	18	23	.10						.05
619.0	624.0	71429	5.0	.0	2D54	3.95	.04	1.40	4.76	10.00	.07		4	18	23	.08						.05
624.0	629.0	71430	5.0	.0	2D4	3.80	.07	4.55	12.71	26.00	.06		4	18	23	.11						.05
629.0	634.0	71431	5.0	.0	2D4	3.34	.11	5.18	11.33	52.50	.12		4	18	23	.12						.05
634.0	639.0	71432	5.0	.0	1D4	2.99	.18	1.29	2.48	33.20	.12		4	18	23	.13						.05

Waste

23

23

40

40

40

50

50

50

50

21

21

DDH: 67-11

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													S.G. W.R.
FROM	TO						CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	
487.0	492.0	71440	5.0	.0	2C0	3.56	.16	3.29	.28	58.00				12	12	25	.50			.26
492.0	497.0	71441	5.0	.0	2D0	3.98	.18	3.75	6.01	53.30				12	12	25	.68			.26
497.0	502.0	71442	5.0	.0	2BE4	3.42	33.08	5.53	4.24	122.60				12	12	25	2.25			.26
502.0	507.0	71443	5.0	.0	2E0	3.41	.17	1.78	1.38	25.10				12	12	25	.84			.26
520.0	525.0	71445	5.0	.0	2EF	3.58	.11	4.99	4.00	90.90	.06	10	18	28			.06			.10
525.0	530.0	71446	5.0	.0	2EF	4.13	50.23	4.55	7.26	70.80	.07	10	18	28			.04			.10
530.0	535.0	71447	5.0	.0	2E4	3.82	.11	6.97	13.29	113.20	.01	10	18	28			.06			.10
535.0	540.0	71448	5.0	.0	2B64	3.28	32.11	2.13	1.92	46.30	.03	10	18	28	11.19					.10
540.0	545.0	71449	5.0	.0	2BE4	3.50	.06	3.23	5.70	48.80	.07	10	18	28			.03			.10
545.0	550.0	71450	5.0	.0	2EF	4.67	50.07	3.75	6.54	27.40	.03	10	18	28			.59			.10
550.0	555.0	71451	5.0	.0	2E24	4.63	.17	3.95	6.28	32.20	.14	4	36	41			.03			.06
555.0	560.0	71452	5.0	.0	2E24	4.72	.15	2.55	3.12	17.00		4	36	41			.30			.06
560.0	565.0	71453	5.0	.0	2E2	4.92	50.20	2.26	3.38	13.80		4	36	41			.05			.06
565.0	570.0	71454	5.0	.0	2E2	4.61	.22	1.01	2.36	27.40	.07	4	36	41			.02			.06
570.0	575.0	71455	5.0	.0	2C7	4.30	.29	1.33	1.81	19.10	.14	15	27	42			.04			.13
575.0	580.0	71456	5.0	.0	2C7	3.99	40.33	.60	.39	12.60	.01	15	27	42			.07			.13
580.0	585.0	71457	5.0	.0	2C7	4.30	.30	.66	.56	11.10	.14	15	27	42			.02			.13
585.0	590.0	71458	5.0	.0	2D7	4.45	.05	1.75	7.00	18.30	.07	15	27	42			.03			.13
590.0	595.0	71459	5.0	.0	2F2	4.45	50.05	1.75	7.00	18.30	.07	15	27	42			.03			.13
595.0	600.0	71460	5.0	.0	2FH4	4.09	.15	1.36	6.23	19.70	.34	5	28	33			.06			.07
600.0	605.0	71461	5.0	.0	2F0	3.75	.07	5.99	8.44	74.00		5	28	33			.13			.07
605.0	610.0	71462	5.0	.0	2E4	4.63	50.02	3.11	6.33	23.40	.07	5	28	33			.04			.07
610.0	615.0	71463	5.0	.0	2E4	4.25	.02	3.38	4.72	18.40	.01	5	28	33			.02			.07
615.0	620.0	71464	5.0	.0	2E4	4.46	.20	3.16	4.81	18.00	.01	6	18	24			.02			.03
620.0	625.0	71465	5.0	.0	2D0	3.36	.27	2.85	4.88	20.70	.14	6	18	25			.17			.03
625.0	630.0	71466	5.0	.0	2D0	2.95	21.08	2.39	7.14	35.70		6	18	25	22.00					.03
630.0	635.0	71467	5.0	.0	2A34	2.96	.12	1.49	3.86	30.90		6	18	24	19.00					.03
635.0	640.0	71468	5.0	.0	2A34	2.69	.02	1.38	3.84	20.80		4	3	7			.21			.03
640.0	645.0	71469	5.0	.0	2A0	2.90	.07	.56	1.22	11.20		2	2	4			.18			.02
645.0	649.0	71470	4.0	.0	2A0	2.70	.07	.59	1.62	13.60		2	2	4			.15			.02
649.0	653.0	71471	4.0	.0	2A4	2.75	21.05	.85	3.85	20.40	.06	3	2	5			.13			.03
653.0	657.0	71472	4.0	.0	2A4	2.90	.06	1.02	4.33	25.60	.27	3	2	5			.13			.03
657.0	662.0	71473	5.0	.0	2A3	2.96	.09	.74	1.25	11.00		3	2	5			.15			.03

DDH: 67-12

---DEPTHS---		SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	---ASSAYS---					S.G. W.R.			
FROM	TO											Po %	Py %	TOT Fe	BAO %	Hg %		Mn %	As %	Ba %
493.0	499.0	71481	6.0	.0	2C01	3.58	33.17	.89	2.88	10.80		6	15	21	.09					.16
499.0	505.0	71482	6.0	.0	2F41	4.64	62.11	6.84	6.00	64.90		6	15	21	1.05					.16
505.0	510.0	71483	5.0	.0	2B01	2.69	1.02	.94	1.23	11.60		6	15	21	2.57					.16
510.0	515.0	71484	5.0	.0	2B01	2.89	32.04	1.89	2.09	33.00		5	8	13	4.31					.21
515.0	520.0	71485	5.0	.0	2B01	2.68	.03	.70	1.07	14.30		5	8	13	3.82					.21
520.0	525.0	71486	5.0	.0	2B41	3.25	.06	2.68	2.86	46.30		5	8	13	4.39					.21
525.0	530.0	71487	5.0	.0	2H49	4.20	.20	7.04	6.20	114.80		5	8	13	3.61					.21
530.0	535.0	71488	5.0	.0	2D01	3.46	32.14	4.94	7.92	84.90		3	7	10	4.98					.14
535.0	540.0	71489	5.0	.0	2B41	2.83	.05	1.47	3.82	28.10		3	7	10	.65					.14
540.0	545.0	71490	5.0	.0	2A01	2.76	.06	1.21	2.02	26.90		3	7	10	.90					.14
545.0	550.0	71491	5.0	.0	2A01	2.72	.02	1.03	2.81	27.80		3	7	10	1.02					.14
550.0	555.0	71492	5.0	.0	2B0	2.80	32.08	1.00	1.97	22.40		6	2	8	.75					.09
555.0	560.0	71493	5.0	.0	2B0	2.80	.05	.84	1.87	16.80		6	2	8	.57					.09
560.0	565.0	71494	5.0	.0	2D01	2.92	.04	1.91	4.01	29.10		6	2	8	.31					.09
565.0	570.0	71495	5.0	.0	2D01	2.99	.02	1.58	3.48	26.00		6	2	8	.06					.09
570.0	575.0	71496	5.0	.0	2D01	2.91	32.03	1.60	3.37	24.30		6	9	16	.17					.12
575.0	580.0	71497	5.0	.0	2D01	2.79	32.05	3.10	5.10	49.20		6	9	16	.19					.12
580.0	585.0	71498	5.0	.0	2D01	2.85	.08	1.38	6.63	21.80		6	9	16	.09					.12
585.0	590.0	71499	5.0	.0	2E29	4.25	.41	4.31	5.14	58.40		6	9	16	.04					.12
590.0	595.0	71500	5.0	.0	2E21	4.74	.09	1.38	2.22	38.00		7	26	34	.02					.15
595.0	600.0	71501	5.0	.0	2E13	4.59	50.17	3.23	4.98	46.80		7	26	34	.02					.15
600.0	605.0	71502	5.0	.0	2E71	4.49	.08	3.93	6.02	44.80		7	26	34	.05					.15
605.0	610.0	71503	5.0	.0	2D4	3.73	.13	4.21	9.35	43.70		7	26	34	.10					.15
610.0	615.0	71504	5.0	.0	2E91	4.55	50.21	1.63	1.67	20.10		7	29	36	.02					.20
615.0	620.0	71505	5.0	.0	2F49	4.62	.30	6.33	10.85	73.70		7	29	36	.02					.20
620.0	625.0	71506	5.0	.0	2E41	4.54	.15	3.68	5.65	37.50		7	29	36	.05					.20
625.0	630.0	71507	5.0	.0	2F91	4.49	50.22	2.42	2.66	29.80		7	29	36	.25					.20
630.0	635.0	71508	5.0	.0	2E47	4.43	.17	2.32	2.54	34.50		7	30	38	.03					.16
635.0	640.0	71509	5.0	.0	2E48	4.40	.56	3.59	3.35	55.90		7	30	38	.27					.16
640.0	645.0	71510	5.0	.0	2E49	4.60	50.65	5.16	6.39	40.60		7	30	38	.02					.16
645.0	650.0	71511	5.0	.0	2E49	4.96	.27	2.53	4.76	24.90		7	30	38	.02					.16
650.0	655.0	71512	5.0	.0	2H49	4.12	70.53	3.14	5.42	46.00		6	13	20	.07					.07
655.0	660.0	71513	5.0	.0	2B49	3.15	.25	1.50	5.06	37.50		6	13	20	.22					.07
660.0	665.0	71514	5.0	.0	2B0	2.70	21.06	.90	2.54	25.10		6	13	20	.21					.07

DDH: 67-30

---DEPTHS---				-----ASSAYS-----																
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
482.8	486.0	71524	3.2	.0 2D3	3.28	.37	5.76	.17	95.10		1.23	4	12	17	.04		.04			
486.0	489.7	71525	3.7	.0 2C3	3.33	.09	.76	1.54	9.40		.34	4	12	17	.03		.04			
489.7	494.0	71526	4.3	.0 2D4	3.26	.21	3.20	8.87	25.30		.69	4	12	17	.06		.04			
494.0	498.7	71527	4.7	.0 2D4	3.38	.19	5.43	8.64	42.60		.27	9	8	18	.05		.20			
498.7	500.0	71528	1.3	.0 2E4	4.88	.05	7.79	6.77	99.20		.14	9	8	18	.04		.20			
500.0	505.0	71529	5.0	.0 2H6	4.37	.25	5.17	4.69	83.40		.07	9	8	18	7.35		.20			
505.0	510.0	71530	5.0	.0 1D49	3.16	.14	3.54	3.66	58.00		.01	9	8	18	2.14		.20			
510.0	514.0	71531	4.0	.0 1D4	2.86	.04	.91	1.53	13.00		.01	9	8	18	2.63		.20			
514.0	517.0	71532	3.0	.0 2A4	3.09	.07	2.20	2.37	30.30		.01	11	13	25	5.98		.33			
517.0	520.0	71533	3.0	.0 2CA	2.83	.04	.69	1.20	11.50		.07	11	13	25	4.94		.33			
520.0	523.6	71534	3.6	.0 2H14	3.75	.20	6.33	6.03	101.10		.07	11	13	25	1.61		.33			
523.6	525.0	71535	1.4	.0 2F64	4.51	.21	5.64	4.90	96.80		.07	11	13	25	5.51		.33			
525.0	529.0	71536	4.0	.0 2H64	4.47	.31	6.43	6.05	96.30		.14	11	13	25	6.47		.33			
529.0	534.0	71537	5.0	.0 2F64	4.59	.12	5.94	5.62	84.70		.21	11	13	25	5.71		.33			
534.0	538.0	71538	4.0	.0 2EH4	4.53	.41	5.01	5.49	71.00		.14	13	10	24	.80		.16			
538.0	540.0	71539	2.0	.0 2H64	3.34	.36	2.38	3.60	33.90		.01	13	10	24	.27		.16			
540.0	545.0	71540	5.0	.0 2H14	4.41	.43	4.86	8.31	57.90		.07	13	10	24	.05		.16			
545.0	550.0	71541	5.0	.0 2D0	3.14	.10	5.78	1.82	113.80		1.10	13	10	24	.12		.16			
550.0	554.0	71542	4.0	.0 2D0	3.10	.07	5.90	1.86	111.90		.07	13	10	24	.20		.16			
554.0	558.0	71543	4.0	.0 2C0	2.92	.08	1.13	2.57	23.40		.01	4	4	9	.25		.05			
558.0	563.0	71544	5.0	.0 2D0	3.01	.11	2.29	4.19	44.30		.07	4	4	9	.42		.05			
563.0	568.0	71545	5.0	.0 2D0	3.12	.23	1.66	5.18	29.00		.07	4	4	9	.28		.05			
568.0	573.0	71546	5.0	.0 2C0	2.87	.08	.73	2.40	12.90			4	4	9	.26		.05			
573.0	578.0	71547	5.0	.0 2C0	2.77	.03	.79	1.87	6.90		.01	3	3	7	.52		.06			
578.0	583.0	71548	5.0	.0 2CA	2.79	.04	.70	1.31	9.70		.07	3	3	7	.36		.06			
583.0	588.0	71549	5.0	.0 2A0	2.94	.06	.84	2.09	12.70		.07	3	3	7	.22		.06			
588.0	593.0	71550	5.0	.0 2A0	2.94	.07	.66	1.53	10.50			3	3	7	.21		.06			
593.0	595.0	71551	2.0	.0 2A0	2.83	.03	.28	.55	4.10			3	3	7	.24		.06			

55.3

.21 4.35 5.38 59.17

DDH: 70-12

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	-ASSAYS-						S.G. W.R.	
FROM	TO												Po %	Py %	TOT Fe	BAO %	Hg %	Mn %		As %
541.0	546.0	71560	5.0	.0	2A0	2.95	.08	1.61	2.52	35.30			7	5	13	.28			.10	
546.0	550.0	71561	4.0	.0	2A0	2.96	.11	.76	1.06	12.60			7	5	13	.24			.10	
550.0	554.5	71562	4.5	.0	2A0	2.96	.23 07	.67	1.25	11.20			7	5	13	.30			.10	
554.5	558.5	71563	4.0	.0	1D41	3.17	.09	2.38	5.61	20.00			7	5	13	.22			.10	
558.5	563.0	71564	4.5	.0	2F4	4.61	.07	7.52	11.65	76.70			5	30	36	.05			.08	
563.0	566.8	71565	3.8	.0	2F4	4.89	.16	6.64	9.00	59.10			5	30	36	.06			.08	
566.8	567.3	71566	.5	.0	2H43	4.60	.49	4.70	6.20	70.00			5	30	36	.03			.08	
567.3	570.9	71567	3.6	.0	2E4	4.71	.50 14	6.48	8.64	55.30			5	30	36	.14			.08	
570.9	572.8	71568	1.9	.0	2F4	4.84	.09	6.26	11.06	66.50			5	30	36	.03			.08	
572.8	576.0	71569	3.2	.0	2E49	4.99	.39	3.66	6.11	46.30			5	30	36	.03			.08	
576.0	581.0	71570	5.0	.0	2F4	4.88	.15	7.31	7.36	66.20			4	26	31	.04			.06	
581.0	586.0	71571	5.0	.0	2F4	4.99	.50 12	7.98	11.40	73.40			4	26	31	.04			.06	
586.0	591.0	71572	5.0	.0	2E4	4.75	.15	4.14	7.10	31.10			4	26	31	.03			.06	
591.0	596.0	71573	5.0	.0	2A0	2.90	.14	.86	1.97	22.70			4	26	31	.40			.06	
596.0	601.0	71574	5.0	.0	2A9	3.03	.21 54	1.63	2.15	50.70			6	5	12	.25			.10	
601.0	604.0	71575	3.0	.0	2A0	2.89	.18	.39	1.14	17.20			6	5	12	.58			.10	

36.5

.15

5.89

9.86

55.12

DDH: 70-13

---DEPTHS---				-----ASSAYS-----																
FROM	TO	SAMPLE INT. NO.	REC. UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe %	BAO %	Hg %	Mn %	As %	Ba %	S.G. W.R.	
400.0	463.5	71582	63.5	.0	****	2.75														
463.5	467.0	71583	3.5	.0	2B0	2.79	.01	.03	.14	1.50				.31						.15
467.0	471.0	71584	4.0	.0	2B0	3.32	.25	.88	1.72	13.20				.11						.15
471.0	475.0	71585	4.0	.0	2D4	3.49	.10	3.28	8.82	25.20				.06						.15
475.0	479.0	71586	4.0	.0	2E0	4.66	.12	6.46	7.34	81.20				.10						.15
479.0	483.0	71587	4.0	.0	2A0	2.84	.04	.76	1.72	16.30				.73						.15
483.0	488.0	71588	5.0	.0	2A0	2.81	.06	.90	2.28	18.20				.45						.05
488.0	493.0	71589	5.0	.0	2A0	2.84	.05	.39	.64	9.60				.45						.05
493.0	498.0	71590	5.0	.0	2A0	2.70	.04	.68	1.08	14.60				.60						.05
498.0	503.0	71591	5.0	.0	2A0	2.72	.04	.51	.82	13.60				.51						.05
528.0	531.5	71593	3.5	.0	2B4	2.98	.03	6.71	5.15	180.00				.04						.07
531.5	535.0	71594	3.5	.0	2B0	2.89	.05	5.38	.39	115.50				.14						.07

Waste
 23
 50
 21
 31
 should be 2E4

Waste

+ 535.0 541.0 waste

DDH: 70-17

					-----ASSAYS-----															
---DEPTHS---	SAMPLE INT. REC.	ROCK	S.G.		CU	Pb	Zn	Ag(AA)	Ag(FA)	Au(FA)	Po	Py	TOT	BAO	Hg	Mn	As	Ba	S.G.	
FROM TO NO.		UNIT	PULP		%	%	%	g/mT	g/mT	g/mT	%	%	Fe	%	%	%	%	%	W.R.	
527.0	529.0	71604	2.0	.0	2B0	.50														
529.0	534.0	71605	5.0	.0	2D0	.50	33	2.50												
534.0	539.0	71606	5.0	.0	2D4	.50		4.50												
539.0	544.0	71607	5.0	.0	2F4	.50		5.00												
544.0	549.0	71608	5.0	.0	2D4	.50	50	9.30												
549.0	554.0	71609	5.0	.0	2D4	.50		4.90												
554.0	559.0	71610	5.0	.0	2D0	.50	21	2.00												
559.0	562.0	71611	3.0	.0	2D0	.50		.90												

32
 should be
 changed to 2F4
 = 6 4.7 6.47
 = 7 4.35 6.28

DDH: 71-01

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													S.G. W.R.
FROM	TO						CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	
614.0	615.5	71622	1.5	.0	2A0	2.90	.06	.83	2.50	14.60			4	4	9	.14		.04		
615.5	616.5	71623	1.0	.0	2H0	3.79	.26	2.93	6.24	58.40			4	4	9	.17		.04		
616.5	620.0	71624	3.5	.0	2A4C	2.94	2.08	2.40	1.77	47.90			4	4	9	.17		.04		
620.0	625.0	71625	5.0	.0	2A4	2.93	.09	1.78	3.60	39.80			4	4	9	.20		.04		
625.0	630.0	71626	5.0	.0	2A0	2.75	.04	.78	1.75	16.10			4	4	9	.13		.04		

2

DDH: 71-02

							-----ASSAYS-----														
DEPTHS	SAMPLE	INT.	REC.	ROCK	S.G.	CU	Pb	Zn	Ag(AA)	Ag(FA)	Au(FA)	Po	Py	TOT	BAO	Hg	Mn	As	Ba	S.G.	
FROM	TO	NO.		UNIT	PULP	%	%	%	g/mT	g/mT	g/mT	%	%	Fe	%	%	%	%	%	W.R.	
532.0	539.0	71634	7.0	2D0	.50	23	1.70	3.40													
539.0	548.0	71635	9.0	2F40	.50	50	5.20	8.00													
548.0	553.0	71636	5.0	2D0	.50	21	1.50	5.00													
553.0	558.0	71637	5.0	2A0	.50	21	1.00	2.10													
558.0	563.0	71638	5.0	2A0	.50	21	1.10	2.80													
563.0	568.0	71639	5.0	2A4	.50		1.30	2.80													
568.0	573.0	71640	5.0	2A4	.50		1.60	2.40													

1A

3.88 6.93

21

3.15 5.75

DDH: 71-03

-----DEPTHS-----							-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe %	BAO %	Hg %	Mn %	As %	Ba %	S.G. W.R.	
583.0	588.0	71649	5.0	.0	2A0	.50	23	1.00	1.20													
588.0	593.0	71650	5.0	.0	2A4	.50		2.40	2.70													
593.0	598.0	71651	5.0	.0	2F4	.50	50	4.50	5.80													
598.0	603.0	71652	5.0	.0	2A4	.50		1.60	2.90													
603.0	608.0	71653	5.0	.0	2A4	.50		1.40	3.20													
608.0	613.0	71654	5.0	.0	2A0	.50	21	.60	1.40													
613.0	618.0	71655	5.0	.0	2A0	.50		.80	1.90													
618.0	623.0	71656	5.0	.0	2A4	.50		1.80	3.30													
623.0	628.0	71657	5.0	.0	2A4	.50	21	1.40	2.70													
628.0	633.0	71658	5.0	.0	2A4	.50		.80	3.90													
633.0	638.0	71659	5.0	.0	2A0	.50		1.50	2.40													

3.45 4.25

DDH: 71-04

							-----ASSAYS-----														
---DEPTHS---	SAMPLE	INT.	REC.	ROCK	S.G.	CU	Pb	Zn	Ag(AA)	Ag(FA)	Au(FA)	Po	Py	TOT	BAO	Hg	Mn	As	Ba	S.G.	
FROM	TO	NO.		UNIT	PULP	%	%	%	g/mT	g/mT	g/mT	%	%	Fe	%	%	%	%	%	W.R.	
504.0	509.0	71667	5.0	.0	2A0	.50		.50													
509.0	514.0	71668	5.0	.0	2A4	.50		2.10													
514.0	519.0	71669	5.0	.0	2A0	.50	23	.60													
519.0	524.0	71670	5.0	.0	2A4	.50		1.90													
524.0	529.0	71671	5.0	.0	2E4	.50	50	3.20													
529.0	534.0	71672	5.0	.0	2E4	.50	50	3.90													9.25
534.0	539.0	71673	5.0	.0	2E4	.50	50	6.00													
539.0	544.0	71674	5.0	.0	2E4	.50	50	1.30													
544.0	548.0	71675	4.0	.0	2E4	.50		1.10													

355 5.7

4.37 4.27

DDH: 71-05

---DEPTHS---					-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
514.0	517.5	71683	3.5	2A0 23	3.04	.32	1.79	.55	69.30			5	18	23	.14					.21
517.5	522.5	71684	5.0	2F4 50	4.05	.18	5.75	6.11	71.60		.27	5	18	23	.64					.21
522.5	527.5	71685	5.0	2F4	4.61	.18	5.18	5.49	83.60		.27	5	18	23	6.80					.21
527.5	533.0	71686	5.5	2D0	2.99	.17	2.46	4.08	57.10		.62	5	18	23	1.29					.21
533.0	536.0	71687	3.0	2DE 21	3.66	.15	3.98	4.86	76.30		.14	5	7	12	.08					.09
536.0	540.0	71688	4.0	2D0	2.94	.18	2.56	5.27	36.80		.27	5	7	12	.75					.09
540.0	544.0	71689	4.0	2D0	3.04	.15	2.06	6.03	39.30		.21	5	7	12	.69					.09
544.0	549.0	71690	5.0	2A4	2.94	.07	1.83	3.53	36.80		.14	5	7	12	.20					.09
549.0	555.0	71691	6.0	2A4 21	2.90	.08	1.67	4.22	34.40		.21	3	3	6	.24					.04
555.0	560.0	71692	5.0	2A4	2.89	.11	3.54	4.48	60.70		.27	3	3	6	.22					.04
560.0	565.0	71693	5.0	2A0	2.69	.08	.89	3.09	26.30		.27	3	3	6	.26					.04

.17 3.72 5.29 61.25

DDH: 72-12

-----DEPTHS-----				-----ASSAYS-----																	
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %	S.G. W.R.	
320.9	324.5	71835	3.6	.0 2D3	3.30	.08	1.85	3.40	29.60			11	10	22	.73		.24				
324.5	332.0	71836	7.5	.0 ****	2.83	.08	.23	.35	6.80			3	3	6	.53		.25				
332.0	334.5	71837	2.5	.0 ****	2.68	.06	.33	.73	9.40			4	4	9	.16		.33				

DDH: 72-13

.86

---DEPTHS---				-----ASSAYS-----																
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
577.0	582.0	71845	5.0	2C0	2.94	23.21	.70	.95	16.10					5 15 20	.30					.12
582.0	587.0	71846	5.0	2E4	4.07	60.19	8.53	6.63	80.40					5 15 20	11.63					.12
587.0	592.0	71847	5.0	2F4	4.12	.11	5.75	9.60	58.30					5 15 20	5.06					.12
592.0	597.0	71848	5.0	2B4	3.32	50.16	4.87	6.96	56.80			2.61	8 19 27	2.03						.27
597.0	602.0	71849	5.0	2F4	4.56	50.19	6.18	6.55				.21	8 19 27	6.35						.27
602.0	607.0	71850	5.0	2F4	4.88	.13	6.28	6.53	87.40			.62	8 19 27	6.87						.27
607.0	612.0	71851	5.0	2F4	4.11	.16	4.97	7.12	74.10			.14	8 19 27	1.70						.27
612.0	617.0	71852	5.0	2B4	3.30	50.25	5.30	5.88	71.20			.21	6 9 16	.77						.12
617.0	622.0	71853	5.0	2F4	3.98	50.34	6.95	9.55	91.20			.21	6 9 16	.31						.12
622.0	627.0	71854	5.0	2B4	3.04	.07	11.39	2.83	192.80			.27	6 9 16	.10						.12
627.0	632.0	71855	5.0	1D4	2.73	.08	.80	.25	16.50				6 9 16	.26						.12
632.0	637.0	71856	5.0	1D4	2.70	waste	.36	.10	5.90				4 4 8	1.07						.05
637.0	642.0	71857	5.0	2B4	3.04	.11	4.00	3.90	86.10			.07	4 4 8	4.59						.05
642.0	647.0	71858	5.0	2B0	2.77	21.08	.62	1.37	16.20				4 4 8	.27						.05
666.5	669.0	71860	2.5	2A3	2.81	.10	.81	1.59	15.50				3 6 10	.08						.26
669.0	673.5	71861	4.5	1D14	2.75	21.10	1.81	1.53	17.30			.01	3 6 10	.26						.26
673.5	678.0	71862	4.5	2A0	2.62	.09	.57	1.50	11.30				3 2 6	.26						.04

+9 .18 6.69 6.85 79.13

waste

DDH: 72-15

-----DEPTHS-----				-----ASSAYS-----																
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
611.0	616.0	71870	5.0	.0 2D7	3.42	.10	1.48	4.88	10.50		.07	8	16	25	.04					.03
616.0	621.0	71871	5.0	.0 2D0	3.39	.06	1.02	3.05	7.60		.14	8	16	25	.06					.03
621.0	626.0	71872	5.0	.0 2D4	4.08	21.05	3.97	9.03	20.50		.21	4	14	19	.10					.03
626.0	631.0	71873	5.0	.0 2D4	3.57	.09	3.14	7.86	22.70		.21	4	14	19	.11					.03
631.0	636.0	71874	5.0	.0 2D0	3.25	.16	2.98	5.72	37.10		.07	4	14	19	.21					.03
636.0	641.0	71875	5.0	.0 2B4	2.96	21.08	1.18	3.49	14.90		.21	4	14	19	.30					.03
641.0	646.0	71876	5.0	.0 2B0	2.94	.11	1.52	2.58	23.80		.01	4	14	19	.39					.03

DDH: 72004

-----DEPTHS-----				-----ASSAYS-----																	
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %	S.G. W.R.	
509.0	511.5	71701	2.5	.0 2J4	3.79	.13	5.04	11.90	77.80			4	4	9	.11						.05
511.5	516.5	71702	5.0	.0 2C0	2.81	.05	1.69	3.67	34.00			4	4	9	.14						.05
516.5	521.0	71703	4.5	.0 2B4	2.69	.04	1.41	4.73	24.60			4	4	9	.10						.05
521.0	526.1	71704	5.1	.0 2B44	2.85	.06	3.53	7.73	60.90			4	4	9	.08						.05

17.1

.06 2.65 6.36 45.95

9.05

DDH: 72007

-----DEPTHS-----				-----ASSAYS-----																
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
345.0	350.0	71786	5.0	.0	****	4.42	.17	4.90	9.16	16.80		7	30	37	.02		.12			
350.0	355.0	71787	5.0	.0	****	4.32	.20	2.30	2.89	8.70		7	33	41	.02		.13			
355.0	360.0	71788	5.0	.0	****	4.52	.21	.98	2.94	6.20		7	33	41	.02		.13			
360.0	365.0	71789	5.0	.0	****	4.63	.26	.74	2.79	5.00		7	33	41	.02		.13			
365.0	370.0	71790	5.0	.0	****	4.62	.27	.50	1.62	5.50		7	33	41	.03		.13			
370.0	375.0	71791	5.0	.0	****	4.78	.30	.62	1.99	6.40		3	38	41	.05		.04			
375.0	380.0	71792	5.0	.0	****	4.88	.23	1.62	3.37	8.00		3	38	41	.01		.04			
380.0	385.0	71793	5.0	.0	****	5.21	.36	3.31	4.97	14.00		3	38	41	.02		.04			
385.0	390.0	71794	5.0	.0	****	4.93	.50	2.92	5.42	16.00		3	38	41	.01		.04			
390.0	395.0	71795	5.0	.0	****	4.79	.45	2.38	5.83	15.00		3	20	24	.01		.03			
395.0	400.0	71796	5.0	.0	****	4.63	.34	2.79	7.13	17.00		3	20	24	.03		.03			
400.0	405.0	71797	5.0	.0	****	4.29	.19	4.43	6.99	42.00		3	20	24	.22		.03			
405.0	410.0	71798	5.0	.0	****	3.27	.11	2.03	5.14	22.00		3	20	24	.26		.03			
410.0	415.0	71799	5.0	.0	****	3.30	.11	2.02	3.94	19.00		5	7	12	.23		.03			
415.0	420.0	71800	5.0	.0	****	3.05	.09	3.78	7.83	28.00		5	7	12	.28		.03			
420.0	425.0	71801	5.0	.0	****	3.34	.07	7.46	15.29	71.00		5	7	12	.07		.03			
425.0	430.0	71802	5.0	.0	****	3.33	.13	3.66	11.72	34.00		5	7	12	.08		.03			
430.0	437.0	71803	7.0	.0	****	2.92	.07	.82	3.14	15.00		4	8	13	.12		.02			

DDH: 73-01

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													S.G. W.R.
FROM	TO						CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe %	BAO %	Hg %	Mn %	As %	
279.0	284.0	71933	5.0	.0	2E42	3.54	.08	2.43	3.34	27.50				4	15	20	.27			.07
284.0	289.0	71934	5.0	.0	2E42	3.96	.18	1.98	2.03	40.20				4	15	20	2.23			.07
289.0	294.0	71935	5.0	.0	1D4	2.65	.04	.05	.06	2.60				4	15	20	.28			.07
294.0	299.0	71936	5.0	.0	1D4	2.77	.04	.07	.08	5.40				4	1	6	.10			.06
299.0	304.0	71937	5.0	.0	0090	3.13	.24	5.50	.14	210.00				4	1	6	.05			.06
304.0	309.0	71938	5.0	.0	1D4	2.86	.13	3.99	.22	92.70				4	1	6	3.53			.06
309.0	313.0	71939	4.0	.0	1D40	2.82	.21	1.84	1.88	55.50				4	1	6	.03			.06
313.0	319.0	71940	6.0	.0	2G40	3.60	.11	4.57	5.89	232.00				6	8	14	13.06			.08
319.0	324.0	71941	5.0	.0	2H40	3.79	.24	2.29	15.40	42.50				6	8	14	.36			.08
324.0	329.0	71942	5.0	.0	2L14	2.92	.05	2.03	4.05	30.40				6	8	14	3.36			.08

DDH: 73-02

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													S.G. W.R.
FROM	TO						CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	
375.0	380.0	71948	5.0	.0	2C0	2.94	.12	.54	1.08	11.70				5	15	20	.17			.15
380.0	385.0	71949	5.0	.0	2D00	3.20	.10	4.06	5.77	42.30				5	15	20	.27			.15
385.0	390.0	71950	5.0	.0	2F01	4.54	.18	4.23	5.77	49.30				5	15	20	2.72			.15
390.0	395.0	71951	5.0	.0	2G48	4.41	.14	4.59	6.46	60.90				5	22	28	17.22			.32
395.0	400.0	71952	5.0	.0	2G48	4.84	.16	5.63	7.11	68.90				5	22	28	7.43			.32
400.0	405.0	71953	5.0	.0	2F48	4.10	.09	4.45	4.92	53.70				5	22	28	.99			.32

DDH: 73028

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													S.G. W.R.
FROM	TO						CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	
235.0	240.0	72001	5.0	.0	****	3.00	.19	.46	.79	9.00				9	15	25	.09		.13	
240.0	245.0	72002	5.0	.0	****	2.88	.04	2.94	3.46	22.00				9	15	25	.13		.13	
245.0	250.0	72003	5.0	.0	****	3.47	.08	2.32	4.43	31.00				9	15	25	.09		.13	
250.0	255.0	72004	5.0	.0	****	4.30	.26	4.93	7.77	58.00				9	15	25	.46		.13	
255.0	260.0	72005	5.0	.0	****	4.61	.24	5.60	8.05	67.00				9	15	25	.14		.13	
260.0	265.0	72006	5.0	.0	****	4.63	.19	6.93	8.82	77.00				7	11	18	1.65		.11	
265.0	270.0	72007	5.0	.0	****	3.23	.22	3.70	7.44	51.00				7	11	18	.26		.11	
270.0	275.0	72008	5.0	.0	****	3.23	.08	3.41	7.12	59.00				7	11	18	.28		.11	
275.0	280.0	72009	5.0	.0	****	3.03	.08	1.66	4.35	34.00				7	11	18	.24		.11	
280.0	285.0	72010	5.0	.0	****	3.01	.12	1.95	3.00	36.00				5	4	9	.24		.03	
285.0	290.0	72011	5.0	.0	****	3.03	.08	1.86	4.79	32.00				5	4	9	.29		.03	
290.0	295.0	72012	5.0	.0	****	3.13	.12	2.12	5.46	38.00				5	4	9	.18		.03	
295.0	300.0	72013	5.0	.0	****	2.69	.05	.82	1.94	20.00				5	4	9	.30		.03	
300.0	305.0	72014	5.0	.0	****	2.81	.04	1.51	2.73	28.00				2	2	5	.18		.05	
305.0	310.0	72015	5.0	.0	****	2.81	.04	.01	.04	2.00				2	2	5	.23		.05	
310.0	315.0	72016	5.0	.0	****	2.74	.05	.87	1.60	12.00				2	2	5	.20		.05	
315.0	320.0	72017	5.0	.0	****	2.92	.09	2.31	4.06	52.00				2	2	5	.29		.05	
320.0	325.0	72018	5.0	.0	****	2.83	.06	1.05	2.19	24.00				3	2	6	.35		.05	
325.0	330.0	72019	5.0	.0	****	2.81	.05	.52	1.18	9.00				3	2	6	.27		.05	

$\frac{20.98}{\div 5} = 4.196$
 $\frac{14}{\div 11} = 1.27$
 $4.91 + 7.84 = 12.75$
 $3.40 + 5.88 = 9.28$
 45.91

DDH: 73029

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----												S.G. W.R.
FROM	TO						CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	
147.0	152.0	72023	5.0	.0	****	3.21	.24	1.44	2.03	40.00			7	9	16	1.00			.07
152.0	157.0	72024	5.0	.0	****	3.66	.15	.77	2.31	24.00			4	20	24	.05			.06
157.0	162.0	72025	5.0	.0	****	3.45	.13	.36	.91	12.00			5	16	22	.06			.06
212.0	217.0	72028	5.0	.0	****	3.63	.41	1.95	.21	56.00			9	16	26	.10			.07
217.0	222.0	72029	5.0	.0	****	3.31	.25	.82	.19	30.00			9	7	17	.15			.10
222.0	227.0	72030	5.0	.0	****	3.55	.19	.15	1.31	15.00			5	18	23	.09			.06
227.0	232.0	72031	5.0	.0	****	2.91	.03	.17	.16	10.00			3	1	5	.19			.07
232.0	237.0	72032	5.0	.0	****	3.59	.20	.03	.40	7.00			5	19	25	.08			.05
237.0	242.0	72033	5.0	.0	****	2.76	.16	.31	.25	10.00			5	4	10	.16			.05
242.0	247.0	72034	5.0	.0	****	3.38	.12	1.75	3.70	24.00			6	10	17	.12			.05
247.0	252.0	72035	5.0	.0	****	3.35	.04	1.97	4.94	22.00			2	13	15	.17			.04
252.0	257.0	72036	5.0	.0	****	3.20	.11	1.98	3.85	24.00			3	7	11	.17			.05
257.0	262.0	72037	5.0	.0	****	3.27	.08	4.75	6.29	66.00			3	9	12	.13			.04
262.0	267.0	72038	5.0	.0	****	3.00	.05	.77	.34	32.00			3	5	8	.13			.06
267.0	272.0	72039	5.0	.0	****	3.42	.05	3.72	7.41	31.00			2	12	15	.08			.03
272.0	277.0	72040	5.0	.0	****	3.22	.18	1.12	1.32	20.00			5	10	16	.08			.03
277.0	282.0	72041	5.0	.0	****	2.94	.18	.62	.96	13.00			5	6	12	.14			.05
282.0	287.0	72042	5.0	.0	****	3.91	.10	3.67	12.45	32.00			4	15	20	.04			.05
287.0	292.0	72043	5.0	.0	****	3.46	.07	6.08	9.38	49.00			4	9	14	.08			.03
292.0	297.0	72044	5.0	.0	****	3.68	.22	2.16	8.79	24.00			9	13	22	.07			.04
297.0	302.0	72045	5.0	.0	****	3.11	.18	2.55	4.37	41.00			7	2	9	.25			.04
302.0	307.0	72046	5.0	.0	****	3.07	.12	1.26	2.16	29.00			5	5	11	.12			.06

DDH: 74-01

---DEPTHS---		SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	ASSAYS						S.G. W.R.				
FROM	TO											Po %	Py %	TOT Fe	BAO %	Hg %	Mn %		As %	Ba %		
314.0	319.0	72052	5.0	.0	2D4(3.00	10	2.97	8.85	53.80		5	11	16	.21		.13					
319.0	324.0	72053	5.0	.0	1D4(3.17	Waste	.03	.66	.68	16.50		5	11	16	.09		.13				
324.0	329.0	72054	5.0	.0	2D4(3.07		.07	6.51	3.18	73.00		4	8	13	.11		.11				
358.0	363.0	72056	5.0	.0	2C7&	3.32		.37	1.92	.70	23.50		6	16	22	.10		.07				
363.0	368.0	72057	5.0	.0	2C7I	3.38	33	.17	1.78	3.00	23.10		6	16	22	.15		.07				
368.0	373.0	72058	5.0	.0	2C3(3.82	40	.11	1.78	2.37	17.20		6	16	22	.08		.07				
373.0	378.0	72059	5.0	.0	2C3	3.02		.18	1.12	1.76	18.50		6	16	22	.16		.07				
391.0	396.0	72061	5.0	.0	2A4(3.21		.10	2.94	6.32	27.00		3	15	18	.11		.07				
396.0	401.0	72062	5.0	.0	2A4	3.40	21	.05	4.08	10.00	32.20		3	15	18	.22		.07				
401.0	406.0	72063	5.0	.0	2D3&	3.30		.10	2.00	4.93	29.70		3	15	18	.13		.07				
406.0	411.0	72064	5.0	.0	2A4	3.25	21	.03	2.73	7.23	22.40		1	15	16	.17		.02				
411.0	416.0	72065	5.0	.0	2A4	3.18		.05	4.70	7.61	50.10		1	15	16	.16		.02				
416.0	421.0	72066	5.0	.0	2A4	3.36		.02	1.94	7.40	19.50		1	15	16	.19		.02				
421.0	426.0	72067	5.0	.0	2A4	3.35		.02	2.42	5.70	20.50		1	15	16	.15		.02				
426.0	431.0	72068	5.0	.0	2A4	3.45	21	.03	1.78	5.22	23.30		1	17	19	.14		.02				
431.0	436.0	72069	5.0	.0	2A4	3.29		.02	.94	3.26	16.10		1	17	19	.17		.02				
436.0	441.0	72070	5.0	.0	2A0	3.23		.03	.58	1.94	13.70		1	17	19	.16		.02				
441.0	446.0	72071	5.0	.0	2A4	3.34	21	.02	1.56	4.36	23.10		1	17	19	.13		.02				
446.0	451.0	72072	5.0	.0	2A0	3.08		.03	.52	.72	24.80		1	18	19	.22		.02				
451.0	456.0	72073	5.0	.0	2A0	3.23		.04	.34	1.84	9.10		1	18	19	.19		.02				
456.0	461.0	72074	5.0	.0	2A0	3.14		.06	.50	1.80	13.50		1	18	19	.18		.02				
461.0	466.0	72075	5.0	.0	2A0	3.28	21	.03	.38	.98	13.50		1	18	19	.14		.02				
466.0	471.0	72076	5.0	.0	2A0	3.19		.03	.54	1.82	17.20		2	22	24	.23		.03				
471.0	476.0	72077	5.0	.0	2A4	3.63		.02	2.59	6.42	19.50		2	22	24	.16		.03				
476.0	481.0	72078	5.0	.0	2F0(4.76	50	.01	2.28	5.61	16.30		2	22	24	.04		.03				
481.0	486.0	72079	5.0	.0	2D4(4.08	21	.02	5.07	10.47	37.10		2	22	24	.05		.03				
486.0	491.0	72080	5.0	.0	2D0	3.34		.06	2.35	5.70	27.70		2	22	24	.13		.03				

Waste Interval
→

DDH: 74-02

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													S.G. W.R.
FROM	TO						CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	
272.0	277.0	72084	5.0	.0	2D0	2.97	.09	1.71	3.99	28.70				3	4	8	.21		.04	
277.0	282.0	72085	5.0	.0	2D0	2.93	.10	1.76	4.59	42.00				3	4	8	.22		.04	
282.0	287.0	72086	5.0	.0	2D0	2.93	.24	1.72	3.17	45.20				3	4	8	.23		.04	
287.0	292.0	72087	5.0	.0	2E40	3.62	.13	5.80	6.92	68.80				7	23	30	.35		.19	
292.0	297.0	72088	5.0	.0	2F4	4.29	.10	5.45	8.36	56.40				7	23	30	.07		.19	
297.0	302.0	72089	5.0	.0	2F4	4.41	.08	6.41	8.72	58.90				7	23	30	.14		.19	
302.0	307.0	72090	5.0	.0	2F40	4.33	.18	7.22	7.32	60.90				7	23	30	.89		.19	

4
 4.30 6.22 7.83
 7 4.30 6.15

DDH: 74-07

					-----ASSAYS-----															
-----DEPTHS---	SAMPLE	INT.	REC.	ROCK	S.G.	CU	Pb	Zn	Ag(AA)	Ag(FA)	Au(FA)	Po	Py	TOT	BAO	Hg	Mn	As	Ba	S.G.
FROM	TO	NO.		UNIT	PULP	%	%	%	g/mT	g/mT	g/mT	%	%	Fe	%	%	%	%	%	W.R.
659.0	664.0	72287	5.0	.0	2C00	2.75	.13	.65	2.24	13.50				3	3	6	.30			.02
664.0	669.0	72288	5.0	.0	2D00	2.85	.05	2.80	6.42	33.50				3	3	6	.26			.02
669.0	674.0	72289	5.0	.0	2D4	2.87	.08	3.74	7.31	38.30				3	3	7	.17			.04
674.0	679.0	72290	5.0	.0	2D0	2.77	21.12	1.61	2.78	23.10				3	3	7	.18			.04
679.0	684.0	72291	5.0	.0	1D40	2.83	.10	.50	2.32	14.20				3	3	7	.19			.04
684.0	689.0	72292	5.0	.0	2D4	2.61	.13	4.03	7.23	51.60				3	3	7	.12			.04
689.0	694.0	72293	5.0	.0	2D40	2.97	.08	4.59	9.52	71.00				5	5	10	.15			.07
694.0	699.0	72294	5.0	.0	1D40	2.85	21.09	1.13	2.35	21.20				5	5	10	.39			.07
699.0	704.0	72295	5.0	.0	2D40	3.33	.06	2.02	7.33	56.10				5	5	10	.08			.07
704.0	709.0	72296	5.0	.0	2D40	3.18	.17	3.82	10.05	60.90				5	5	10	.14			.07
709.0	714.0	72297	5.0	.0	2D0&	2.79	.07	1.59	5.33	25.10				3	3	7	.19			.05
714.0	719.0	72298	5.0	.0	2D4&	2.81	21.07	3.36	7.58	54.20				3	3	7	.14			.05
719.0	724.0	72299	5.0	.0	2D4&	3.00	.08	3.40	7.60	41.60				3	3	7	.12			.05
724.0	729.0	72300	5.0	.0	1D40	2.82	.02	.29	.10	7.10				3	3	7	.27			.05
729.0	734.0	72301	5.0	.0	1D40	2.96	.07	1.61	2.45	29.50				3	3	7	.22			.05

DDH: 74-08

DEPTHS		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	ASSAYS													S.G. W.R.
FROM	TO						CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe %	BAO %	Hg %	Mn %	As %	
395.0	400.0	72307	5.0	.0	2ED	3.59	.17	1.12	4.60	19.30			.07	5	20	26	.14	.07		
400.0	405.0	72308	5.0	.0	2DE4	4.12	.14	5.69	12.94	68.30			.14	5	20	26	.08	.07		
405.0	410.0	72309	5.0	.0	2E14	4.20	.33	5.23	8.03	75.10			.14	5	20	26	.30	.07		
410.0	415.0	72310	5.0	.0	2D0	3.77	.14	1.28	3.13	27.60			.21	2	22	24	.08	.02		
415.0	420.0	72311	5.0	.0	2EC	3.81	.22	.15	.14	10.90			.14	2	22	24	.07	.02		
420.0	425.0	72312	5.0	.0	2C0	3.45	.29	1.01	.14	30.20			.48	2	22	24	.13	.02		
425.0	430.0	72313	5.0	.0	2C0	3.01	.39	.51	.18	20.80				2	21	23	.10	.02		
430.0	435.0	72314	5.0	.0	2CF	3.84	.20	3.31	3.36	42.30			.27	4	22	26	.14	.28		
435.0	440.0	72315	5.0	.0	1D/2E	3.86	.17	5.44	4.39	63.60			.41	4	22	26	.42	.28		
440.0	445.0	72316	5.0	.0	2ED4	3.68	.20	5.93	4.29	65.70			.41	4	22	26	.71	.28		
445.0	450.0	72317	5.0	.0	2GD4	4.31	.13	6.05	5.76	82.00				4	22	26	12.11	.28		
450.0	455.0	72318	5.0	.0	2B0	2.81	.04	.99	1.04	13.90				4	10	14	4.41	.17		
455.0	460.0	72319	5.0	.0	2B0	2.69	.04	.59	.72	10.10				4	10	14	3.97	.17		
460.0	465.0	72320	5.0	.0	2B0	2.77	.04	.40	.48	7.00				4	10	14	2.18	.17		
465.0	470.0	72321	5.0	.0	2B4	4.67	.31	5.26	4.97	76.50				4	10	14	.09	.17		
470.0	475.0	72322	5.0	.0	2B0	2.69	.03	.28	.39	5.50				4	4	9	2.26	.22		
482.0	487.0	72324	5.0	.0	2D0	3.12	.08	4.64	4.21	70.30				4	4	9	8.21	.22		
487.0	492.0	72325	5.0	.0	2D0	3.01	.12	3.38	3.37	53.40				.07	21	16	37	4.47	.16	
492.0	497.0	72326	5.0	.0	2H4	4.25	.29	4.74	7.81	69.60	*			.07	21	16	37	1.37	.16	
497.0	502.0	72327	5.0	.0	2H4	4.33	.35	2.99	3.53	40.50				.01	21	16	37	.05	.16	
502.0	507.0	72328	5.0	.0	2EG	4.63	.21	2.40	3.22	34.60				.01	21	16	37	1.27	.16	
507.0	512.0	72329	5.0	.0	2E0	4.80	.10	1.23	.85	16.40				.01	12	30	42	.04	.10	
512.0	517.0	72330	5.0	.0	2E4	4.86	.14	2.25	3.10	24.20				.01	12	30	42	.12	.10	
517.0	522.0	72331	5.0	.0	2E4	4.80	.12	5.19	7.48	47.70	*			.01	12	30	42	.05	.10	
522.0	527.0	72332	5.0	.0	2E4	4.26	.29	3.08	6.83	30.90	*			.01	12	30	42	.06	.10	
527.0	532.0	72333	5.0	.0	2E4	4.13	.27	1.57	3.50	20.80				.07	14	22	36	.10	.12	
532.0	537.0	72334	5.0	.0	2F0	4.55	.16	2.05	3.29	20.90				.07	14	22	36	.02	.12	
537.0	542.0	72335	5.0	.0	2HF	4.36	.26	2.49	4.69	20.10				.21	14	22	36	.03	.12	
542.0	547.0	72336	5.0	.0	2D0	3.00	.13	1.18	2.94	18.50				.14	14	22	36	.31	.12	
547.0	552.0	72337	5.0	.0	2A4	2.83	.12	.90	3.26	27.40				.14	5	6	12	.27	.06	
552.0	557.0	72338	5.0	.0	2D0	3.18	.20	1.88	3.35	48.70				.14	5	6	12	.22	.06	
557.0	562.0	72339	5.0	.0	2A4	2.86	.10	1.53	3.74	37.30				.34	5	6	12	.31	.06	
562.0	567.0	72340	5.0	.0	2B4/0	3.67	.05	29.40	2.12	642.20	*			.14	5	6	12	.20	.06	
567.0	572.0	72341	5.0	.0	2A4	2.86	.14	2.88	4.74	66.70	*			.07	5	6	12	.24	.06	

3.44 3.72
7.16

should be changed to 1D1 (1D19)

include inside in side of floor

23

22

60

32

70

50

21

21

18 ore

20 W

20 ore

18 W

-5

*

*

DDH: 74-10

---DEPTHS---		SAMPLE	INT.	REC.	ROCK	S.G.	ASSAYS												S.G.		
FROM	TO	NO.			UNIT	PULP	CU	Pb	Zn	Ag(AA)	Ag(FA)	Au(FA)	Po	Py	TOT	BAO	Hg	Mn	As	Ba	W.R.
							%	%	%	g/mT	g/mT	g/mT	%	%	Fe	%	%	%	%	%	%
227.7	230.0	72377	2.3	.0	2CF	3.38	10	2.33	3.78	34.10		.03	3	8	11	.64					.06
<i>Waste</i> 230.0	234.8	72378	4.8	.0	2B0	2.85	.03	.22	.20	2.70		.03	3	8	11	4.80					.06
276.0	281.0	72380	5.0	.0	2E3	3.99	.39	.66	.48	19.50			6	18	25	.37					.18
281.0	286.0	72381	5.0	.0	2GE	4.78	50.06	5.43	9.33	62.70		.07	6	18	25	33.59					.18
286.0	296.0	72382	10.0	.0	2GE	4.52	.26	3.20	6.23	44.80		.14	12	19	32	18.38					.10
296.0	301.0	72383	5.0	.0	2E4	4.41	.48	4.89	5.51	84.70		.07	12	19	32	.26					.10
301.0	306.0	72384	5.0	.0	2H4	4.16	50.51	4.20	3.73	56.90		.07	12	19	32	1.05					.10
306.0	311.0	72385	5.0	.0	2E3	3.90	.47	2.20	1.71	40.10		.14	8	29	37	.18					.20
311.0	316.0	72386	5.0	.0	2E8	4.72	.14	1.14	2.29	19.90		.48	8	29	37	.10					.20
316.0	321.0	72387	5.0	.0	2E8	3.87	.27	.47	.83	6.50			8	29	37	.11					.20
321.0	326.0	72388	5.0	.0	2E1	4.52	40.34	1.02	.62	20.50			8	29	37	.02					.20
326.0	331.0	72389	5.0	.0	2E1	4.27	.30	1.53	.48	19.80			7	27	35	.08					.14
331.0	336.0	72390	5.0	.0	2E4	3.91	.26	1.93	2.70	25.60			7	27	35	.04					.14
336.0	341.0	72391	5.0	.0	2F0	4.12	.21	3.28	4.98	45.90		.34	7	27	35	.02					.14
341.0	346.0	72392	5.0	.0	2E4	4.18	.24	1.31	4.76	16.50		.27	7	27	35	.04					.14
346.0	351.0	72393	5.0	.0	2E4	4.11	50.19	3.83	6.20	31.70		.27	5	30	35	.02					.21
351.0	356.0	72394	5.0	.0	2F1	4.57	.37	1.83	1.19	24.40		.07	5	30	35	.03					.21
356.0	361.0	72395	5.0	.0	2E4	3.99	.25	1.83	3.19	18.00		.55	5	30	35	.03					.21
361.0	366.0	72396	5.0	.0	2E8	4.16	50.32	3.18	5.54	21.40		.07	5	30	35	.02					.21
366.0	371.0	72397	5.0	.0	2F0	4.39	.27	3.04	2.75	16.10		.01	4	30	34	.03					.16
371.0	376.0	72398	5.0	.0	2E4	4.62	1.15	4.34	4.55	30.40		.01	4	30	34	.02					.16
376.0	381.0	72399	5.0	.0	2CE	3.78	.31	1.10	1.50	11.50		.96	4	30	34	.02					.16
381.0	386.0	72400	5.0	.0	2CE	3.86	.23	1.10	2.17	12.40		.41	4	30	34	.02					.16
386.0	391.0	72401	5.0	.0	2CE	4.06	50.06	3.87	12.75	14.20		.01	3	22	25	.04					.04
391.0	396.0	72402	5.0	.0	2F4	3.81	.06	4.09	10.43	14.60		.07	3	22	25	.11					.04
396.0	401.0	72403	5.0	.0	2E4	3.47	.04	2.61	7.54	16.60		.07	3	22	25	.13					.04
401.0	406.0	72404	5.0	.0	2F0	4.34	50.11	3.06	6.24	19.80		.21	3	22	25	.05					.04
406.0	411.0	72405	5.0	.0	2E4	3.87	.02	2.68	8.45	16.30		.07	3	22	25	.08					.06
411.0	416.0	72406	5.0	.0	2FE4	4.53	50.03	5.25	9.75	28.00		.41	3	22	25	.04					.06
416.0	421.0	72407	5.0	.0	2E4	4.05	.04	3.42	6.74	19.30		.14	3	22	25	.08					.06
421.0	426.0	72408	5.0	.0	2C0	2.75	.04	.20	.48	4.90		.07	3	22	25	.35					.06
426.0	431.0	72409	5.0	.0	2C0	3.04	.05	.23	.43	8.90		.14	5	15	20	.17					.04
431.0	436.0	72410	5.0	.0	2C0	3.32	21.14	1.83	.81	20.90		.07	5	15	20	.12					.04
436.0	441.0	72411	5.0	.0	2CD	3.51	.06	1.97	5.14	14.30		.14	5	15	20	.12					.04
441.0	446.0	72412	5.0	.0	2D4	3.18	.25	3.59	10.27	21.10		.14	5	15	20	.10					.04
446.0	451.0	72413	5.0	.0	2A0	2.75	21.15	.50	1.56	9.20			5	6	12	.24					.05
451.0	456.0	72414	5.0	.0	2A0	3.13	.19	.28	1.88	12.80			5	6	12	.18					.05

DDH: 74-11

-----DEPTHS-----					-----ASSAYS-----																
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %	S.G. W.R.	
159.5	164.7	72419	5.2	.0 ****	3.28	.14	.15	6.70			.03	10	11	21	.32						.12
164.7	167.1	72420	2.4	.0 1D49	2.96	.09	2.33	1.44	56.80		.03	10	11	21	1.30						.12
167.1	170.5	72421	3.4	.0 2D0	3.45	.06	2.52	4.50	49.20		.03	6	6	13	1.05						.12
170.5	175.5	72422	5.0	.0 2L0	2.81	.02	.06	.08	1.00		.03	6	6	13	2.47						.12
175.5	177.6	72423	2.1	.0 2D6	3.62	.07	2.97	1.59	50.00		.03	6	6	13	14.02						.12
177.6	182.8	72424	5.2	.0 2L0	2.81	.03	.29	.18	4.20		.03	6	6	13	1.82						.12
182.8	185.0	72425	2.2	.0 2B4	3.52	.05	4.40	4.70	70.80			6	6	13	11.75						.12
185.0	188.1	72426	3.1	.0 2L0	2.99	.03	.62	.55	10.70			6	6	13	6.12						.12
188.1	193.0	72427	4.9	.0 2L0	2.97	.03	.33	.10	1.80			5	4	9	3.90						.07
193.0	196.2	72428	3.2	.0 0Q0	2.88	.01	.18	.08	.10			5	4	9	7.44						.07
196.2	201.0	72429	4.8	.0 1D0	2.73	.01	.10	.13	.10			5	4	9	4.03						.07
201.0	206.0	72430	5.0	.0 2DH4	3.32	.12	3.78	7.73	53.30			5	4	9	1.69						.07
206.0	211.0	72431	5.0	.0 2F4	4.67	.11	7.14	11.90	50.10			3	30	33	.18						.05
211.0	216.0	72432	5.0	.0 2F4	4.73	.02	3.28	8.71	21.80			3	30	33	.02						.05
216.0	221.0	72433	5.0	.0 2F4	4.80	.08	3.45	9.17	25.00			3	30	33	.02						.05
221.0	226.0	72434	5.0	.0 2F4	4.75	.09	6.47	10.90	48.10			3	30	33	.05						.05
226.0	231.0	72435	5.0	.0 2F4	4.86	.05	5.10	12.06	36.70			3	30	33	.02						.05
231.0	236.0	72436	5.0	.0 2F4	4.81	.07	3.44	6.68	24.50			2	30	33	.02						.05
236.0	241.0	72437	5.0	.0 2F4	4.84	.06	3.56	6.65	31.90			2	30	33	.03						.05
241.0	246.0	72438	5.0	.0 2HF4	4.20	.40	1.90	6.50	36.20			2	30	33	.29						.05
246.0	251.0	72439	5.0	.0 2HF4	4.37	.29	4.49	8.61	41.60			2	30	33	2.00						.05
251.0	256.0	72440	5.0	.0 2F0	4.00	.20	2.34	5.31	17.40			16	10	26	.18						.08
256.0	261.0	72441	5.0	.0 2D0	3.09	.13	1.81	6.43	17.10			16	10	26	.37						.08
261.0	266.0	72442	5.0	.0 2D0	3.16	.10	4.08	3.76	56.60			16	10	26	.46						.08
266.0	271.0	72443	5.0	.0 2D0	3.05	.11	1.81	2.64	29.00			16	10	26	.38						.08
271.0	276.0	72444	5.0	.0 2D0	2.95	.07	2.37	3.09	39.40			4	5	10	.23						.04
276.0	281.0	72445	5.0	.0 2D0	2.98	.07	4.00	4.45	72.20			4	5	10	.23						.04
281.0	286.0	72446	5.0	.0 2DA	2.78	.06	1.46	4.18	29.70			4	5	10	.29						.04
286.0	291.0	72447	5.0	.0 2A0	2.87	.21	.98	.84	52.30			4	5	10	7.19						.04
291.0	296.0	72448	5.0	.0 2A0	2.64	.05	.76	1.14	9.70			2	2	4	.47						.03
296.0	300.0	72449	4.0	.0 2B4	2.77	.04	1.16	4.06	15.80			2	2	4	.23						.03

DDH: 74-17

---DEPTHS---				-----ASSAYS-----																
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
484.0	489.0	72541	5.0	.0	2D4	3.43	33.08	5.49	15.00	32.90										
489.0	494.0	72542	5.0	.0	2E49	4.55	.20	6.48	7.90	72.50										
494.0	499.0	72543	5.0	.0	2Q96	3.54	60.17	3.63	4.52	51.40										
499.0	504.0	72544	5.0	.0	2Q96	2.98	.04	.68	.94	10.00										
504.0	509.0	72545	5.0	.0	2Q89	3.51	.27	3.91	6.13	55.50										
509.0	514.0	72546	5.0	.0	2G40	4.56	60.16	5.15	6.52	78.80										
514.0	519.0	72547	5.0	.0	2G49	4.58	.33	5.76	6.43	89.00										
519.0	524.0	72548	5.0	.0	2E40	4.71	.17	6.17	7.05	105.80										
524.0	529.0	72549	5.0	.0	2E40	4.30	50.08	5.02	6.26	80.30										
529.0	534.0	72550	5.0	.0	2B40	2.89	50.10	2.54	4.87	35.10										
534.0	539.0	72551	5.0	.0	2E41	3.47	.18	3.33	4.70	57.60										
539.0	544.0	72552	5.0	.0	2D08	2.96	.06	2.85	4.26	79.70										
544.0	549.0	72553	5.0	.0	2D08	3.00	21.15	3.26	3.70	66.80										
549.0	554.0	72554	5.0	.0	2D08	3.12	.09	4.27	3.77	106.00										
554.0	559.0	72555	5.0	.0	2D08	3.06	.06	2.00	4.75	53.60										
559.0	564.0	72556	5.0	.0	2D08	3.10	21.06	7.01	4.32	555.00										
564.0	569.0	72557	5.0	.0	0Q90	2.91	.04	2.91	2.16	62.50										
569.0	574.0	72558	5.0	.0	2D50	3.00	21.15	2.33	3.31	53.40										
574.0	579.0	72559	5.0	.0	2B00	2.84	21.11	1.14	2.10	45.90										
579.0	585.0	72560	6.0	.0	0Q90	2.84	.04	1.89	.28	27.40										

=18 113 4.04 5.37

DDH: 74-18

---DEPTHS---				-----ASSAYS-----																
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
124.0	129.0	72563	5.0	.0 2D0	3.65	23.11	2.33	5.85	30.60			.14	11	13	25	.15				.09
129.0	134.0	72564	5.0	.0 2E4	4.64	.16	3.57	6.39	40.40			.07	11	13	25	.05				.09
134.0	139.0	72565	5.0	.0 2H4	4.22	70.40	3.19	4.65	45.80			.07	11	13	25	.03				.09
139.0	144.0	72566	5.0	.0 2H4	4.58	.37	5.05	6.82	67.20			.14	11	13	25	.05				.09
144.0	149.0	72567	5.0	.0 2B0	4.76	.32	1.80	2.98	21.90			.01	10	7	17	.07				.04
149.0	154.0	72568	5.0	.0 2B4	3.22	.20	.90	4.11	14.40			.07	10	7	17	.57				.04
154.0	159.0	72569	5.0	.0 2B4	3.03	21.11	1.29	2.78	21.60			.01	10	7	17	.45				.04
159.0	164.0	72570	5.0	.0 2A0	3.06	.14	1.20	2.73	19.40			.21	10	7	17	.78				.04
164.0	168.0	72571	4.0	.0 2A4	3.11	.03	1.37	6.07	23.30			.27	3	7	11	.48				.03
168.0	173.0	72572	5.0	.0 2A4	3.05	21.02	2.13	1.99	45.60			.62	3	7	11	.45				.03
173.0	178.0	72573	5.0	.0 2A0	2.99	.05	1.40	2.52	28.80			.34	3	7	11	.42				.03
178.0	183.0	72574	5.0	.0 2A0	2.68	21.02	.66	1.57	12.30				3	7	11	.60				.03
183.0	188.0	72575	5.0	.0 2A0	2.75	21.06	.75	1.49	19.40				3	4	7	.37				.02
188.0	191.5	72576	3.5	.0 2A0	2.88	.07	.37	.22	11.70				3	4	7	.24				.02

DDH: 74-19

					-----ASSAYS-----															
---DEPTHS---	SAMPLE INT.	REC.	ROCK	S.G.	CU	Pb	Zn	Ag(AA)	Ag(FA)	Au(FA)	Po	Py	TOT	BAO	Hg	Mn	As	Ba	S.G.	
FROM	TO	NO.	UNIT	PULP	%	%	%	g/mT	g/mT	g/mT	%	%	Fe	%	%	%	%	%	W.R.	
231.0	236.0	72582	5.0	.0	2C0	3.34	.40	.80	.11	15.60			8	8	17	.02			.05	
236.0	241.0	72583	5.0	.0	2D0	2.78	.09	1.20	5.32	49.40			.27	8	8	17	.05		.05	
241.0	246.0	72584	5.0	.0	2D0	3.39 ³³	.14	2.33	3.07	48.00			.07	8	8	17	.33		.05	
246.0	251.0	72585	5.0	.0	2D0	3.79	.09	2.83	3.73	37.50			.14	5	10	16	.24		.06	
251.0	256.0	72586	5.0	.0	2C0	3.37	.16	1.48	1.92	36.00			.07	5	10	16	.81		.06	
256.0	261.0	72587	5.0	.0	2C2	2.98	.08	.80	2.02	21.70			.62	5	10	16	1.03		.06	
261.0	266.0	72588	5.0	.0	2D0	2.99 ²	.10	1.58	2.68	38.90			.07	5	10	16	.63		.06	
266.0	271.0	72589	5.0	.0	2D0	3.06	.11	2.63	4.93	68.40			.07	4	4	9	.62		.04	
271.0	276.0	72590	5.0	.0	2A0	2.96	.10	1.04	2.80	36.80			.34	4	4	9	.47		.04	
276.0	281.0	72591	5.0	.0	2A0	2.77	.04	.66	1.22	13.90				4	4	9	.50		.04	
281.0	286.0	72592	5.0	.0	2A0	2.98 ²	.11	.60	1.14	19.80				4	4	9	.23		.04	
286.0	288.0	72593	2.0	.0	2A0	2.84	.07	.42	.66	13.80				4	4	9	.30		.04	

DDH: 74-20

---DEPTHS---				-----ASSAYS-----																	
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %	S.G. W.R.	
219.0	224.0	72599	5.0	.0 2C0	3.45	.42	.50	.44	10.20			2	24	26	.11		.04				
224.0	229.0	72600	5.0	.0 2C0	3.49	.10	.46	2.95	7.90			.14	2	24	26	.12		.04			
229.0	234.0	72601	5.0	.0 2C0	4.29	.33	.66	2.24	13.30			.01	2	24	26	.12		.04			
234.0	239.0	72602	5.0	.0 2E3	4.94	.02	.28	.74	6.50			.48	3	22	25	.03		.16			
239.0	244.0	72603	5.0	.0 2E4	4.37	.17	5.70	6.79	81.00			.34	3	22	25	.36		.16			
244.0	249.0	72604	5.0	.0 2D6	3.19	.10	2.30	2.56	37.90			.48	3	22	25	2.25		.16			
249.0	254.0	72605	5.0	.0 2D6	3.17	.04	3.39	3.39	67.60			.14	3	22	25	6.07		.16			
254.0	259.0	72606	5.0	.0 2E4	4.17	.23	3.43	4.76	52.30			.21	21	21	43	.31		.14			
259.0	264.0	72607	5.0	.0 2H4	4.50	.40	2.20	3.51	29.60			1.78	21	21	43	.03		.14			
264.0	269.0	72608	5.0	.0 2H4	4.54	.33	3.43	5.24	41.00			.14	21	21	43	.02		.14			
269.0	274.0	72609	5.0	.0 2H4	4.74	.20	2.35	4.14	27.00			.07	21	21	43	.10		.14			
274.0	279.0	72610	5.0	.0 2E4	4.64	.45	3.14	4.90	19.90			.07	6	34	40	.12		.05			
279.0	284.0	72611	5.0	.0 2H4	4.98	.07	3.02	5.44	16.50			.01	6	34	40	.04		.05			
284.0	289.0	72612	5.0	.0 2EF	4.88	.03	3.80	5.24	20.20			.21	6	34	40	.03		.05			
289.0	294.0	72613	5.0	.0 2EF	4.78	.04	2.30	4.00	15.60			.34	6	34	40	.08		.05			
294.0	299.0	72614	5.0	.0 2BC	3.18	.14	1.80	3.49	33.90			.34	6	34	40	.42		.05			

Handwritten notes in the right margin of the table:
 - Next to row 239.0-244.0: 20'
 - Next to row 244.0-249.0: 0.14, 3.71, 4.33, 5.17 (9.09)
 - Next to row 279.0-284.0: 20'
 - Next to row 284.0-289.0: 3.07, 4.90 (7.97)

DDH: 74-21

							-----ASSAYS-----													
---DEPTHS---	SAMPLE INT.	REC.	ROCK	S.G.	CU	Pb	Zn	Ag(AA)	Ag(FA)	Au(FA)	Po	Py	TOT	BAO	Hg	Mn	As	Ba	S.G.	
FROM TO NO.			UNIT	PULP	%	%	%	g/mT	g/mT	g/mT	%	%	Fe	%	%	%	%	%	W.R.	
99.0	104.0	72619	5.0	.0	2F0	4.37	.18	3.70	3.41	40.50										
104.0	109.0	72620	5.0	.0	2F4	3.10	.22	6.20	6.14	76.50										
109.0	114.0	72621	5.0	.0	2F0	3.52	.15	4.08	4.87	55.00										
114.0	119.0	72622	5.0	.0	2D34	3.43	.11	4.10	5.92	59.50										
119.0	124.0	72623	5.0	.0	2C0	3.02	.10	.42	1.08	6.80										
124.0	127.0	72624	3.0	.0	2E47	4.38	.32	1.56	2.63	24.60										
131.5	135.7	72626	4.2	.0	2C3	2.79	.08	1.17	1.16	25.30										
135.7	136.3	72627	.6	.0	2H4	4.03	.42	5.46	7.25	83.50										
139.0	144.0	72629	5.0	.0	2B4	4.03	.42	5.46	7.25	83.50										
144.0	149.0	72630	5.0	.0	2A4	3.23	.25	3.70	5.06	58.40										
149.0	154.0	72631	5.0	.0	2A0	2.71	.09	.51	.89	14.60										
154.0	159.0	72632	5.0	.0	2A0	2.56	.06	.26	.34	10.30										
159.0	164.0	72633	5.0	.0	2A0	2.69	.05	2.96	.97	59.90										
164.0	169.0	72634	5.0	.0	2A0	2.57	.03	.30	.23	13.90										
169.0	174.0	72635	5.0	.0	2A0	2.66	.06	.34	.75	10.00										
174.0	179.0	72636	5.0	.0	2A0	2.65	.04	.94	1.21	14.20										
179.0	184.0	72637	5.0	.0	2A0	2.57	.03	1.13	1.51	12.60										
184.0	189.0	72638	5.0	.0	2A0	2.65	.09	1.29	2.55	18.30										
189.0	194.5	72639	5.5	.0	2A0	2.78	.15	.92	1.33	15.80										

include
waste

DDH: 74005

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													S.G. W.R.
FROM	TO						CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	
290.0	295.0	72145	5.0	.0	****	3.45	.06	4.99	9.57	23.00			3	27	30	.09		.04		
295.0	300.0	72146	5.0	.0	****	3.49	.06	4.78	12.90	33.50			3	15	19	.09		.04		
300.0	305.0	72147	5.0	.0	****	3.24	.05	2.43	7.24	25.00			3	15	19	.09		.04		
305.0	310.0	72148	5.0	.0	****	3.25	.06	1.36	.88	18.80			3	15	19	.06		.04		
310.0	315.0	72149	5.0	.0	****	3.29	.06	.28	1.24	7.70			3	15	19	.10		.04		
315.0	320.0	72150	5.0	.0	****	3.22	.29	.18	1.52	12.20			6	7	13	.20		.06		
320.0	325.0	72151	5.0	.0	****	2.80	.08	1.58	2.16	29.50			6	7	13	.21		.06		

DDH: 74006

---DEPTHS---			SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													S.G. W.R.
FROM	TO	CU %						Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %	
282.0	287.0	72205	5.0	.0	****	4.66	.03	7.73	16.30	33.70			2	26	28	.02		.02			
287.0	292.0	72206	5.0	.0	****	4.83	.02	8.08	12.83	36.10			2	26	28	.02		.02			
292.0	297.0	72207	5.0	.0	****	4.50	.03	8.96	15.00	38.30			2	20	22	.06		.02			
297.0	302.0	72208	5.0	.0	****	3.65	.07	7.47	18.60	35.00			2	20	22	.07		.02			
302.0	307.0	72209	5.0	.0	****	4.42	.05	5.06	8.55	26.40			3	25	28	.02		.02			
307.0	312.0	72210	5.0	.0	****	3.95	.07	7.17	16.90	31.90			4	12	17	.03		.02			
312.0	317.0	72211	5.0	.0	****	4.07	.11	6.33	15.60	28.80			4	16	20	.02		.03			
317.0	322.0	72212	5.0	.0	****	4.88	.03	5.36	7.45	24.30			1	35	37	.01		.01			
322.0	327.0	72213	5.0	.0	****	4.76	.07	3.03	5.66	15.10			1	35	37	.01		.01			
327.0	332.0	72214	5.0	.0	****	4.13	.06	2.52	7.00	17.30			1	35	37	.04		.01			
332.0	337.0	72215	5.0	.0	****	3.21	.06	.82	1.88	9.70			3	26	29	.17		.04			
337.0	342.0	72216	5.0	.0	****	3.54	.06	2.28	4.78	18.10			3	26	29	.04		.04			
342.0	347.0	72217	5.0	.0	****	3.95	.07	.95	2.71	12.80			3	26	29	.03		.04			
347.0	352.0	72218	5.0	.0	****	4.73	.03	2.40	3.95	19.60			3	26	29	.01		.04			
352.0	357.0	72219	5.0	.0	****	4.51	.03	1.72	4.78	16.30			4	30	34	.02		.06			
357.0	362.0	72220	5.0	.0	****	4.34	.08	1.15	3.72	19.20			4	30	34	.06		.06			
362.0	367.0	72221	5.0	.0	****	3.86	.07	.65	3.02	9.40			4	30	34	.05		.06			
367.0	372.0	72222	5.0	.0	****	3.83	.06	2.35	4.38	21.60			4	30	34	.05		.06			
372.0	377.0	72223	5.0	.0	****	3.33	.10	1.73	4.22	16.70			4	18	22	.19		.02			
377.0	382.0	72224	5.0	.0	****	4.03	.05	4.53	11.75	29.00			4	20	24	.08		.02			
382.0	387.0	72225	5.0	.0	****	4.20	.03	3.90	10.00	25.40			4	22	26	.03		.02			
387.0	392.0	72226	5.0	.0	****	3.53	.05	2.31	9.82	19.00			4	18	22	.06		.02			
392.0	397.0	72227	5.0	.0	****	3.09	.05	1.20	3.98	14.00			6	12	18	.13		.07			
397.0	402.0	72228	5.0	.0	****	3.52	.09	3.33	8.79	25.30			6	12	18	.13		.07			
402.0	407.0	72229	5.0	.0	****	3.31	.23	4.82	5.16	56.40			6	12	18	.15		.07			

DDH: 74009

---DEPTHS---	SAMPLE	INT.	REC.	ROCK	S.G.	-----ASSAYS-----														S.G.		
						FROM	TO	NO.	UNIT	PULP	CU	Pb	Zn	Ag(AA)	Ag(FA)	Au(FA)	Po	Py	TOT		BAO	Hg
						%	%	%	g/mT	g/mT	g/mT	%	%	Fe	%	%	%	%	%	%	%	
171.0	176.0	72345	5.0	.0	****	3.30	.10	1.55	5.01	23.70		7	21	29	.17				.21			
176.0	181.0	72346	5.0	.0	****	3.91	.21	2.06	4.83	29.10		7	21	29	.09				.21			
181.0	186.0	72347	5.0	.0	****	4.40	.22	5.99	8.01	74.60		7	21	29	.11				.21			
186.0	191.0	72348	5.0	.0	****	4.63	.22	6.37	7.04	83.60		7	21	29	.60				.21			
191.0	196.0	72349	5.0	.0	****	4.36	.13	2.98	3.92	43.00		7	21	29	.38				.21			
196.0	201.0	72350	5.0	.0	****	4.25	.26	5.60	6.78	74.50		6	35	42	.22				.26			
201.0	206.0	72351	5.0	.0	****	4.59	.13	4.19	4.99	57.70		6	35	42	.25				.26			
206.0	211.0	72352	5.0	.0	****	4.54	.18	5.98	5.83	82.30		6	35	42	4.51				.26			
211.0	216.0	72353	5.0	.0	****	4.41	.32	4.79	4.59	75.60		6	35	42	.30				.26			
216.0	221.0	72354	5.0	.0	****	4.61	.24	7.75	8.10	93.90		7	23	30	.10				.50			
221.0	226.0	72355	5.0	.0	****	5.02	.18	7.42	7.36	102.50		2	18	21	10.21				.09			
226.0	231.0	72356	5.0	.0	****	4.75	.11	7.64	9.46	89.00		2	18	21	26.78				.09			
231.0	236.0	72357	5.0	.0	****	4.68	.07	6.97	8.46	72.40		2	18	21	29.28				.09			
236.0	241.0	72358	5.0	.0	****	4.65	.13	3.56	4.65	37.90		3	20	23	11.23				.16			
241.0	246.0	72359	5.0	.0	****	4.75	.24	8.43	8.13	100.70		3	20	23	11.30				.16			
246.0	251.0	72360	5.0	.0	****	4.55	.18	10.10	8.67	123.20		3	20	23	14.82				.16			
251.0	256.0	72361	5.0	.0	****	4.76	.11	7.14	8.17	73.50		3	20	23	32.13				.16			
256.0	261.0	72362	5.0	.0	****	4.86	.37	2.20	1.82	26.10		4	34	38	.76				.03			
261.0	266.0	72363	5.0	.0	****	5.35	.19	3.25	4.34	22.20		4	34	38	.05				.03			
266.0	271.0	72364	5.0	.0	****	4.70	.13	5.59	7.59	41.60		4	34	38	.06				.03			
271.0	276.0	72365	5.0	.0	****	4.68	.51	3.42	6.81	40.60		4	34	38	.09				.03			
276.0	281.0	72366	5.0	.0	****	4.45	.68	3.00	5.58	34.80		11	3	15	.07				.04			
281.0	286.0	72367	5.0	.0	****	2.87	.18	2.10	4.39	28.80		11	3	15	.27				.04			
286.0	291.0	72368	5.0	.0	****	2.72	.10	1.18	1.38	9.30		11	3	15	.23				.04			
291.0	296.0	72369	5.0	.0	****	2.69	.05	1.38	2.26	8.60		11	3	15	.24				.04			
296.0	301.0	72370	5.0	.0	****	2.76	.14	1.30	1.88	13.70		4	2	6	.21				.04			
301.0	306.0	72371	5.0	.0	****	2.67	.12	2.10	2.67	21.60		4	2	6	.26				.04			
306.0	311.0	72372	5.0	.0	****	2.78	.13	1.92	2.19	30.60		4	2	6	.29				.04			

DDH: 75-03

					-----ASSAYS-----																
DEPTH	DEPTH	SAMPLE INT.	REC.	ROCK	S.G.	CU	Pb	Zn	Ag(AA)	Ag(FA)	Au(FA)	Po	Py	TOT	BAO	Hg	Mn	As	Ba	S.G.	
FROM	TO	NO.		UNIT	PULP	%	%	%	g/mT	g/mT	g/mT	%	%	Fe	%	%	%	%	%	W.R.	
529.0	535.0	72715	6.0	.0	2D9&	4.00	.39	3.01	5.26	35.70			3	18	21	.11					.07
535.0	540.0	72716	5.0	.0	2D4&	3.42	.10	3.30	7.80	3.40			3	18	21	.18					.07
540.0	545.0	72717	5.0	.0	2E11	3.76	.07	1.91	4.41	18.50			3	18	21	.10					.07
545.0	550.0	72718	5.0	.0	2C8&	3.48	.17	1.83	3.90	18.50			3	18	21	.10					.07
550.0	555.0	72719	5.0	.0	2C8&	3.94	.24	.21	.77	10.30			3	24	27	.05					.13
555.0	560.0	72720	5.0	.0	2C89	3.51	.20	.22	1.08	3.40			3	24	27	.15					.13
560.0	565.0	72721	5.0	.0	2C39	4.07	.39	.09	1.06	2.70			3	24	27	.06					.13
565.0	570.0	72722	5.0	.0	2C9&	3.60	.24	.60	2.22	8.20			3	24	27	.09					.13
570.0	575.0	72723	5.0	.0	2C0&	3.58	.11	.20	.40	10.30			1	21	23	.09					.02
575.0	580.0	72724	5.0	.0	2C51	3.51	.19	.06	.14	1.40			1	21	23	.10					.02
580.0	585.0	72725	5.0	.0	2C5	3.58	.18	.29	.90				1	21	23	.11					.02
585.0	590.0	72726	5.0	.0	2C39	3.91	.21	.48	.70	4.50			1	21	23	.08					.02
590.0	595.0	72727	5.0	.0	2C39	3.89	.42	.35	.86	3.40			3	16	20	.06					.04
595.0	600.0	72728	5.0	.0	2D0&	3.64	.06	2.30	6.36	7.50			3	16	20	.09					.04
600.0	605.0	72729	5.0	.0	2D4&	3.42	.13	3.20	7.58	32.20			3	16	20	.13					.04
605.0	610.0	72730	5.0	.0	2C0&	2.87	.14	1.40	1.90	17.80			3	16	20	.31					.04
610.0	615.0	72731	5.0	.0	2L01	2.92	.15	.55	1.31	6.90			3	4	7	.20					.04
615.0	620.0	72732	5.0	.0	2L0	2.83	.02	.27	.95	8.90			3	4	7	.12					.04
620.0	625.0	72733	5.0	.0	2L0	2.67	.02	.03	.17	6.20			3	4	7	.15					.04
625.0	630.0	72734	5.0	.0	2A01	2.82	.04	.86	1.15	15.80			3	4	7	.16					.04
630.0	635.0	72735	5.0	.0	2A4	2.75	.09	1.65	3.90	32.90			3	4	7	.32					.03
635.0	640.0	72736	5.0	.0	2A4	2.88	.12	.84	3.60	19.50			3	4	7	.41					.03
640.0	645.0	72737	5.0	.0	2A4	2.89	.06	1.10	3.60	22.30			3	4	7	.32					.03
645.0	650.0	72738	5.0	.0	2A0	2.89	.13	1.27	2.20	25.70			3	4	7	.27					.03
650.0	655.0	72739	5.0	.0	2C01	2.87	.11	.72	1.63	25.00			2	3	6	.24					.02
655.0	660.0	72740	5.0	.0	2C01	2.86	.09	.70	1.32	20.60			2	3	6	.20					.02
660.0	665.0	72741	5.0	.0	2A4	2.75	.10	1.60	3.62	34.00			2	1	4	.22					.01
665.0	670.0	72742	5.0	.0	2A4	2.84	.06	1.06	3.19	16.40			2	1	4	.18					.01
670.0	675.8	72743	5.8	.0	2A41	2.83	.12	2.38	4.93	41.90			3	2	5	.16					.04
675.8	677.9	72744	2.1	.0	2D9&	2.95	.27	1.57	4.11	25.80			3	2	5	.12					.04

SECTIONS
 121+000 1/2 120+070

DDH: 75-04

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----												S.G. W.R.
FROM	TO						CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe %	BAO %	Hg %	Mn %	
210.5	218.0	72747	7.5	.0	****	3.17	.07	.30	.53	6.80			9	14	23	.10			.12
218.0	223.0	72748	5.0	.0	2E74	4.25	<i>50</i> .26	3.85	5.72	74.70			9	14	23	.11			.12
223.0	228.0	72749	5.0	.0	2E74	4.06	<i>50</i> .21	5.78	9.95	85.70			9	14	23	.16			.12
228.0	233.0	72750	5.0	.0	2EH4	4.21	<i>50</i> .28	4.55	7.30	58.30			14	22	37	.17			.09
<i>waste</i> 233.0	237.5	72751	4.5	.0	2EH4	4.32	<i>50</i> .31	3.40	4.95	56.00			14	22	37	.15			.09
283.0	288.0	72753	5.0	.0	2B4	3.60	.19	8.82	.52	148.10			6	16	23	.20			.26
288.0	293.0	72754	5.0	.0	2E4	4.16	<i>50</i> .22	2.70	3.71	26.10			5	31	37	.11			.39
293.0	298.0	72755	5.0	.0	2E4	3.85	<i>50</i> .34	3.60	4.02	38.40			5	31	37	.16			.39
298.0	303.0	72756	5.0	.0	2E4	4.34	.36	2.55	1.68	28.00			5	31	37	.13			.39
303.0	308.0	72757	5.0	.0	2E0	4.67	.39	.70	.56				5	31	37	.15			.39
308.0	313.0	72758	5.0	.0	2E4	4.46	<i>50</i> .33	2.18	2.14	17.80			4	34	39	.14			.24
313.0	318.0	72759	5.0	.0	2E4	4.67	<i>50</i> .16	2.40	2.70	26.10			4	34	39	.13			.24
318.0	323.0	72760	5.0	.0	2E4	4.52	.41	3.30	2.76	40.50			4	34	39	.14			.24
323.0	328.0	72761	5.0	.0	2E4	4.63	<i>50</i> .33	2.23	2.73	21.90			4	34	39	.13			.24
328.0	333.0	72762	5.0	.0	2E4	3.97	<i>50</i> .13	2.96	5.70	33.60			1	28	30	.14			.05
333.0	338.0	72763	5.0	.0	2E0	3.76	.24	1.07	1.98	22.60			1	28	30	.14			.05
338.0	343.0	72764	5.0	.0	2E0	4.06	.27	1.41	1.62	19.90			1	28	30	.21			.05
343.0	348.0	72765	5.0	.0	2E0	4.04	<i>40</i> .30	1.30	2.10	6.20			1	28	30	.15			.05
348.0	353.0	72766	5.0	.0	2E0	3.82	.30	1.00	1.16	2.10			1	28	30	.14			.02
353.0	358.0	72767	5.0	.0	2E4	3.59	.34	1.53	2.66	15.10			1	28	30	.14			.02
358.0	363.0	72768	5.0	.0	2E0	3.96	<i>40</i> .24	1.13	2.07	5.40			1	28	30	.15			.02
363.0	368.0	72769	5.0	.0	2E4	4.10	.13	3.47	5.63	20.60			1	28	30	.15			.02
368.0	373.0	72770	5.0	.0	2E0	4.24	.42	1.26	1.78	3.40			3	30	34	.13			.17
373.0	378.0	72771	5.0	.0	2E0	4.15	<i>40</i> .26	1.07	1.13	3.40			3	30	34	.14			.17
378.0	383.0	72772	5.0	.0	2E0	4.27	.38	1.95	1.91	8.60			3	30	34	.13			.17
383.0	388.0	72773	5.0	.0	2E4	4.25	.26	2.33	3.15	21.20			3	30	34	.12			.17
388.0	393.0	72774	5.0	.0	2E1	3.89	<i>50</i> .22	1.05	2.35	8.90			3	24	27	.14			.16
393.0	398.0	72775	5.0	.0	2E4	3.96	.25	1.75	5.19	6.20			3	24	27	.17			.16
398.0	403.0	72776	5.0	.0	2E4	3.83	.18	1.03	3.74	3.40			3	24	27	.15			.16
403.0	408.0	72777	5.0	.0	2E1	4.07	<i>50</i> .37	.37	2.63				3	24	27	.14			.16
408.0	413.0	72778	5.0	.0	2F4	4.21	.14	3.78	8.50	17.10			3	21	25	.14			.05
413.0	418.0	72779	5.0	.0	2D4	3.42	.09	3.28	8.35	20.60			3	21	25	.08			.05
418.0	423.0	72780	5.0	.0	2F4	4.13	<i>50</i> .06	4.80	11.30	19.90			3	21	25	.06			.05
423.0	426.2	72781	3.2	.0	2D4	3.57	.13	4.45	6.76	21.90			3	21	25	.24			.05

DDH: 75-09

---DEPTHS---					-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
579.0	584.0	72969	5.0	.0	2A14	3.29	.04	1.96	3.58	24.00		1	7	9	.17					.02
584.0	589.0	72970	5.0	.0	2A0	2.93	21.07	.86	2.64	15.09		1	7	9	.23					.02
589.0	594.0	72971	5.0	.0	2A0	2.81	.05	.80	2.64	11.00		1	7	9	.23					.02
594.0	599.0	72972	5.0	.0	2A0	2.93	.05	.40	1.69	11.00		1	6	7	.20					.02
599.0	609.0	72973	10.0	.0	2A0	2.91	21.05	.71	1.74	18.50		1	6	7	.20					.02
609.0	614.0	72974	5.0	.0	2A0	2.87	.05	.59	2.02	13.69		1	6	7	.20					.02
614.0	619.0	72975	5.0	.0	2A0	2.95	.05	.49	2.02	15.80		2	7	10	.22					.02
619.0	624.0	72976	5.0	.0	2D0	3.00	.14	1.39	2.87	28.10		2	7	10	.20					.02
624.0	629.0	72977	5.0	.0	2A0	3.00	21.17	.28	1.06	11.59		2	7	10	.17					.02
629.0	634.0	72978	5.0	.0	2A0	2.85	.05	.34	.34	18.50		2	7	10	.20					.02
634.0	639.0	72979	5.0	.0	2A0	3.06	.08	1.64	1.28	20.60		12	2	14	.16					.04
639.0	644.0	72980	5.0	.0	2C75	3.04	.20	.28	.62	12.30		12	2	14	.14					.04
644.0	649.0	72981	5.0	.0	2C75	3.02	21.16	1.69	2.27	21.89		12	2	14	.14					.04
649.0	654.0	72982	5.0	.0	2A7	3.00	.13	1.52	3.00	15.09		12	2	14	.11					.04
654.0	659.0	72983	5.0	.0	2A7	3.00	.17	.26	.07	11.00		10	1	12	.14					.02
659.0	664.0	72984	5.0	.0	2C7	3.25	.17	3.10	6.25	34.29		10	1	12	.19					.02
664.0	669.0	72985	5.0	.0	1D21	2.79	21.10	1.04	.67	28.80		10	1	12	.23					.02
669.0	674.0	72986	5.0	.0	1D21	2.89	.10	.24	.80	9.59		10	1	12	.23					.02
674.0	679.0	72987	5.0	.0	1D21	2.91	.08	1.01	1.82	17.80		4	3	7	.20					.01
679.0	684.0	72988	5.0	.0	2A0	2.91	21.08	1.35	1.37	17.10		4	3	7	.14					.01
684.0	689.0	72989	5.0	.0	2L@	2.85	.11	.62	1.78	10.30		4	3	7	.14					.01
689.0	694.0	72990	5.0	.0	2D0&	2.93	.08	3.02	4.20	67.50		4	3	7	.11					.01
694.0	699.0	72991	5.0	.0	2D0&	3.00	.13	2.47	3.16	38.39		3	3	6	.08					
699.0	704.0	72992	5.0	.0	1D4	2.91	21.05	3.37	5.05	40.50		3	3	6	.13					
704.0	709.0	72993	5.0	.0	2A0	2.85	.02	1.03	1.87	14.40		3	3	6	.16					

DDH: 75-10

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	---ASSAYS---				Hg %	Mn %	As %	Ba %	S.G. W.R.
FROM	TO												Po %	Py %	TOT Fe	BAO %					
485.0	490.0	72996	5.0	.0	2D35	3.31	.05	1.73	4.62	13.00			2	14	17	.11				.01	
490.0	495.0	72997	5.0	.0	2D35	3.35	21.05	1.39	3.72	8.19			1	22	24	.11				.01	
495.0	500.0	72998	5.0	.0	2D35	3.37	.04	1.43	3.72	26.69			1	16	18	.11				.02	
500.0	505.0	72999	5.0	.0	2D35	3.35	.07	1.05	4.21	15.09			1	16	18	.11				.02	
505.0	510.0	73000	5.0	.0	2D35	2.91	.04	1.69	5.20	7.49			1	16	18	.10				.02	
510.0	515.0	73001	5.0	.0	2D35	4.09	21.02	1.87	3.29	21.30				16	17	.11				.01	
515.0	520.0	73002	5.0	.0	2D35	3.02	.05	1.85	5.19	10.30				16	17	.11				.01	
520.0	525.0	73003	5.0	.0	2C35	3.12	.14	.35	1.10	8.90				16	17	.11				.01	
525.0	530.0	73004	5.0	.0	2C35	3.10	21.08	.83	2.83	3.39				16	17	.08				.01	
530.0	535.0	73005	5.0	.0	2D35	3.41	.10	2.70	4.54	49.39				19	20	.05				.02	
535.0	540.0	73006	5.0	.0	2C31	4.06	.16	1.36	.75	21.89				19	20	.04				.02	
540.0	545.0	73007	5.0	.0	2E19	3.56	40.24	.62	1.79	4.09				19	20	.04				.02	
545.0	550.0	73008	5.0	.0	2E11	3.66	.11	.31	.92	4.09				19	20	.08				.02	
550.0	555.0	73009	5.0	.0	2C35	3.62	21.05	.55	1.71	9.59			1	17	18	.08				.02	
555.0	560.0	73010	5.0	.0	2C35	3.29	.05	.61	1.46	15.09			1	17	18	.13				.02	
560.0	565.0	73011	5.0	.0	2C35	3.25	.05	1.71	1.96	20.60			1	17	18	.14				.02	
565.0	570.0	73012	5.0	.0	2C3&	3.25	21.04	1.59	2.24	5.50			1	17	18	.16				.02	
570.0	575.0	73013	5.0	.0	2C3&	3.41	.05	1.11	2.10	5.50			1	14	16	.17				.02	
575.0	580.0	73014	5.0	.0	2D51	3.35	.05	1.64	1.53	5.50			1	14	16	.14				.02	
580.0	585.0	73015	5.0	.0	2D5	3.33	21.08	1.77	7.92	10.30			1	14	16	.17				.02	
585.0	590.0	73016	5.0	.0	2C35	3.27	.05	.65	2.14	9.59			1	14	16	.05				.02	
590.0	595.0	73017	5.0	.0	2C3&	3.68	.08	1.04	2.37	13.69			1	20	21	.08				.02	
595.0	600.0	73018	5.0	.0	2D3&	3.56	21.05	3.60	7.20	20.60			1	20	21	.14				.02	
600.0	605.0	73019	5.0	.0	2C3&	3.49	.04	.75	2.31	25.69			1	20	21	.11				.02	
605.0	610.0	73020	5.0	.0	2E0&	3.47	.02	1.07	1.81	36.70			1	20	21	.05				.02	
610.0	613.5	73021	3.5	.0	2D4	4.05	21.05	3.68	10.59	363.50			2	16	19	.07				.02	
624.5	630.0	73023	5.5	.0	2D0&	3.25	.11	1.55	3.58	122.79			2	16	19	.14				.02	
630.0	635.0	73024	5.0	.0	1D41	2.99	.08	2.54	3.18	110.40			3	3	7	.14				.05	
635.0	638.0	73025	3.0	.0	2B4	3.18	.14	1.65	4.98	24.00			3	3	7	.11				.05	

DDH: 75-11

							-----ASSAYS-----														
DEPTHS	SAMPLE	INT.	REC.	ROCK	S.G.	CU	Pb	Zn	Ag(AA)	Ag(FA)	Au(FA)	Po	Py	TOT	BAO	Hg	Mn	As	Ba	S.G.	
FROM	TO	NO.		UNIT	PULP	%	%	%	g/mT	g/mT	g/mT	%	%	Fe	%	%	%	%	%	W.R.	
477.0	480.0	73030	3.0	2A0	2.95	.16	.40	.75						3 7 10	.16						.02
480.0	485.0	73031	5.0	2A4	3.04	.08	1.49	2.60	8.19					3 7 10	.10						.02
485.0	490.0	73032	5.0	2A4 ²³	2.60	.05	2.50	5.33	24.00					3 7 10	.14						.02
490.0	495.0	73033	5.0	2A4	2.81	.15	1.60	2.93	6.20					11 11 22	.26						.02
495.0	500.0	73034	5.0	2F4&	3.87	.17	3.60	6.29	33.60					11 11 22	.17						.02
500.0	505.0	73035	5.0	2F4& ⁷⁰	4.30	.31	5.50	7.08	41.79					11 11 22	.08						.02
505.0	510.0	73036	5.0	2H49	3.50	.35	4.02	5.78	35.00					11 11 22	.39						.02
510.0	515.0	73037	5.0	10E0 v. waste	2.73	.01	.10	.08	4.79					22 5 27	.85						.01
515.0	520.0	73038	5.0	2H48	3.81	.32	5.19	7.89	55.49					22 5 27	.23						.10
520.0	525.0	73039	5.0	2H48	5.21	.44	6.84	9.59	41.79					22 5 27	.40						.10
525.0	530.0	73040	5.0	2H48 ⁷⁰	3.89	.34	6.61	9.69	68.59					22 5 27	.46						.10
530.0	535.0	73041	5.0	2H48	3.79	.44	5.50	7.58	68.59					12 21 33	.40						.10
535.0	540.0	73042	5.0	2F4	4.25	.32	5.58	8.98	61.70					12 21 33	.17						.10
540.0	545.0	73043	5.0	2F4 ⁵⁰	4.62	.08	4.90	8.10	54.89					12 21 33	.11						.10
545.0	550.0	73044	5.0	2F4	4.00	.11	4.96	7.78	60.39					12 21 33	.08						.10
550.0	555.0	73045	5.0	2H48 ⁷⁰	4.17	.64	4.98	7.17	58.29					21 7 28	.41						.08
555.0	560.0	73046	5.0	2D79Z1	3.31	.23	2.02	5.23	35.00					21 7 28	.14						.08
560.0	565.0	73047	5.0	2H49	3.60	.61	4.09	7.09	76.09					21 7 28	.10						.08
565.0	570.0	73048	5.0	2H49 ⁷⁰	3.79	.49	3.89	4.59	96.70					21 7 28	1.74						.08

.48 .29 4.08 6.32 46.17

DDH: 75001

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----												S.G. W.R.	
FROM	TO						CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %		As %
39.0	42.0	72643	3.0	.0	****	3.00	.28	5.93	6.61	118.60			8	12	21	.02				.07
42.0	47.0	72644	5.0	.0	****	2.96	.38	1.60	2.87	19.20			8	12	21	.02				.07
47.0	52.0	72645	5.0	.0	****	2.96	.22	1.27	1.52	13.70			8	12	21	.03				.07
52.0	57.0	72646	5.0	.0	****	3.26	.45	.08	.12				8	12	21	.02				.07
57.0	62.0	72647	5.0	.0	****	3.23	.41	.37	.38	1.70			8	12	21	.03				.07
62.0	67.0	72648	5.0	.0	****	3.51	.29	.31	.56	1.40			10	13	23	.02				.11
67.0	72.0	72649	5.0	.0	****	3.17	.27	.02	.16				10	13	23	.02				.11
72.0	77.0	72650	5.0	.0	****	3.05	.24	.10	.13				10	13	23	.16				.11
77.0	82.0	72651	5.0	.0	****	3.67	.28	2.48	2.60	21.20			10	13	23	3.79				.11
82.0	87.0	72652	5.0	.0	****	4.15	.40	5.01	7.00	92.60			10	21	31	.18				.32
87.0	92.0	72653	5.0	.0	****	4.59	.18	4.93	6.30	113.80			10	21	31	3.43				.32
92.0	97.0	72654	5.0	.0	****	4.60	.15	7.39	6.40	87.80			10	21	31	16.17				.32
97.0	102.0	72655	5.0	.0	****	4.46	.23	5.71	6.00	87.10			10	21	31	8.67				.32
102.0	107.0	72656	5.0	.0	****	4.62	.13	5.24	5.25	53.50			1	33	35	20.49				.06
107.0	112.0	72657	5.0	.0	****	4.71	.16	3.30	5.48	43.90			1	33	35	.20				.06
112.0	117.0	72658	5.0	.0	****	4.14	.14	1.77	2.00	32.20			1	33	35	.04				.06
117.0	122.0	72659	5.0	.0	****	4.63	.30	2.23	1.70	24.70			1	33	35	.02				.06
122.0	127.0	72660	5.0	.0	****	4.71	.33	2.54	2.89	17.10			4	33	38	.01				.17
127.0	132.0	72661	5.0	.0	****	4.51	.49	1.86	2.94	28.10			4	33	38	.02				.17
132.0	137.0	72662	5.0	.0	****	4.78	.26	3.98	3.78	43.90			4	33	38	1.78				.17
137.0	142.0	72663	5.0	.0	****	4.45	.20	2.63	2.73	34.30			4	33	38	4.13				.17
142.0	147.0	72664	5.0	.0	****	4.02	.17	1.31	1.30	10.30			3	31	34	.03				.10
147.0	152.0	72665	5.0	.0	****	4.28	.11	1.95	2.32	12.30			3	31	34	.02				.10
152.0	157.0	72666	5.0	.0	****	4.36	.21	3.05	3.25	27.40			3	31	34	5.11				.10
157.0	162.0	72667	5.0	.0	****	4.65	.27	4.80	4.98	61.70			3	31	34	4.64				.10
162.0	167.0	72668	5.0	.0	****	4.58	.20	3.35	4.13	24.70			4	34	38	.05				.14
167.0	172.0	72669	5.0	.0	****	4.61	.19	6.39	11.30	30.90			4	34	38	.05				.14
172.0	177.0	72670	5.0	.0	****	4.61	.69	.56	1.52	12.30			4	34	38	.02				.14
177.0	182.0	72671	5.0	.0	****	4.71	.40	2.30	3.60	9.60			4	34	38	.01				.14
182.0	187.0	72672	5.0	.0	****	4.52	.68	1.58	2.40	13.00			2	35	37	.01				.05
187.0	192.0	72673	5.0	.0	****	4.69	.34	2.42	4.94	12.30			2	35	37	.02				.05
192.0	197.0	72674	5.0	.0	****	4.12	.57	4.44	3.44	31.50			2	35	37	.05				.05
197.0	202.0	72675	5.0	.0	****	4.74	.17	3.90	7.20	26.70			2	35	37	.03				.05
202.0	207.0	72676	5.0	.0	****	4.61	.33	4.63	6.52	25.40			1	33	34	.02				.03
207.0	212.0	72677	5.0	.0	****	4.55	.30	2.75	3.58	21.90			1	33	34	.03				.03
212.0	217.0	72678	5.0	.0	****	4.11	.36	3.17	4.78	25.40			1	33	34	.05				.03
217.0	222.0	72679	5.0	.0	****	4.32	.20	2.72	7.40	18.50			1	33	34	.04				.03
222.0	227.0	72680	5.0	.0	****	2.77	.07	1.25	3.10	17.10			2	5	7	.07				.02
227.0	233.0	72681	6.0	.0	****	2.75	.14	1.28	2.43	35.00			2	5	7	.07				.02

DDH: 75002

---DEPTHS---		SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													
FROM	TO					CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %
513.5	515.0	72684	1.5	2H49	4.33	.68	5.74	7.65	91.20				9	25	35	.30		.29	
515.0	520.0	72685	5.0	60 2F4	4.70	.17	6.60	7.24	96.00				9	25	35	.02		.29	
520.0	525.0	72686	5.0	2F4	5.63	.08	5.98	7.44	71.30				9	25	35	.99		.29	
525.0	530.0	72687	5.0	2H469	4.44	.36	5.60	7.21	58.30				9	25	35	2.03		.29	
530.0	535.0	72688	5.0	60 2E4(2)	4.79	.31	4.57	6.58	50.10				16	21	38	1.00		.25	
535.0	540.0	72689	5.0	2F467	4.60	.11	5.66	6.30	69.30				16	21	38	5.64		.25	
540.0	545.0	72690	5.0	2H49	4.50	.41	4.86	5.80	54.90				16	21	38	.39		.25	
545.0	550.0	72691	5.0	70 2H49(5.80	.35	5.42	7.10	59.00				16	21	38	1.84		.25	
550.0	555.0	72692	5.0	2H49(5.76	.36	5.94	6.36	78.90				13	24	38	5.30		.42	
555.0	560.0	72693	5.0	2H496	4.39	.65	4.44	4.49	52.10				13	24	38	1.08		.42	
560.0	565.0	72694	5.0	2E489	4.55	.24	3.72	4.15	37.00				13	24	38	.66		.42	
565.0	570.0	72695	5.0	60 2E49	4.59	.28	3.14	3.00	42.50				13	24	38	.74		.42	
570.0	575.0	72696	5.0	2F69(4.76	.33	3.52	3.47	58.30				13	24	38	1.28		.42	
575.0	580.0	72697	5.0	2D9(2	3.88	.43	3.16	3.12	48.00				3	29	32	3.17		.11	
580.0	585.0	72698	5.0	60 2F0	4.61	.09	4.23	5.02	44.60				3	29	32	.15		.11	
585.0	590.0	72699	5.0	2G4	5.36	.19	5.64	6.38	52.80				3	29	32	17.16		.11	
590.0	595.0	72700	5.0	2E0	4.71	.10	2.42	1.40	15.80				3	29	32	.05		.11	
595.0	600.0	72701	5.0	2E9	4.73	.31	2.44	1.85	15.80				11	17	29	.05		.10	
600.0	605.0	72702	5.0	2D9	3.41	.41	1.42	3.90	17.80				11	17	29	.08		.10	
605.0	610.0	72703	5.0	2H09	3.25	.62	1.90	3.40	25.40				11	17	29	.21		.10	
610.0	615.0	72704	5.0	50 2D459	4.40	.28	3.10	7.12	47.30				11	17	29	.12		.10	
615.0	620.0	72705	5.0	2A0	2.76	.04	.81	2.56	10.30				3	20	23	.22		.02	
620.0	625.0	72706	5.0	2E4	4.03	.03	2.42	7.70	26.10				3	20	23	.09		.02	
625.0	630.0	72707	5.0	50 2E4	5.55	.04	1.81	6.54	8.20				3	20	23	.10		.02	
630.0	635.0	72708	5.0	2E4	3.86	.15	3.46	6.40	22.60				3	20	23	.10		.02	
635.0	640.0	72709	5.0	2D459	2.90	.22	.40	7.25	11.00				12	2	14	.14		.03	
640.0	645.0	72710	5.0	21 2A4	2.67	.11	.81	3.32	16.40				12	2	14	.14		.03	
645.0	650.0	72711	5.0	2A4	2.70	.10	1.27	3.10	17.10				12	2	14	.14		.03	
650.0	654.7	72712	4.7	2A49	3.83	1.11	2.12	4.25	56.90				12	2	14	.06		.03	

DDH: 75007

---DEPTHS---			SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----												S.G. W.R.
FROM	TO	CU %						Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	
49.0	50.0	72842	1.0	.0	****	3.56	.24	.20	.05	11.00			2	22	24	.03		.02		
50.0	55.0	72843	5.0	.0	****	3.36	.12	.18	.96	2.00			2	22	24	.04		.02		
55.0	60.0	72844	5.0	.0	****	3.58	.17	.76	2.20	2.00			1	26	28	.02		.02		
60.0	65.0	72845	5.0	.0	****	3.66	.06	4.55	3.71	87.80			1	26	28	.03		.02		
65.0	70.0	72846	5.0	.0	****	4.03	.04	2.23	4.62	8.90			1	26	28	.03		.02		
70.0	75.0	72847	5.0	.0	****	3.64	.04	1.94	4.00	8.90			1	26	28	.05		.02		
75.0	80.0	72848	5.0	.0	****	3.73	.04	1.12	3.00	8.90			1	22	24	.04		.01		
80.0	85.0	72849	5.0	.0	****	3.49	.05	1.76	4.14	11.00			1	22	24	.08		.01		
85.0	90.0	72850	5.0	.0	****	3.51	.06	1.78	4.38	17.10			1	22	24	.04		.01		
90.0	95.0	72851	5.0	.0	****	3.50	.04	1.50	4.85	13.70			1	22	24	.06		.01		
95.0	100.0	72852	5.0	.0	****	3.41	.03	.25	1.49	4.80			2	17	19	.06		.02		
100.0	105.0	72853	5.0	.0	****	3.46	.05	3.76	4.20	30.90			2	17	19	.06		.02		
105.0	110.0	72854	5.0	.0	****	3.22	.03	1.12	4.73	17.10			2	17	19	.07		.02		
110.0	115.0	72855	5.0	.0	****	3.27	.03	1.50	4.53	17.10			2	17	19	.06		.02		
115.0	120.0	72856	5.0	.0	****	3.44	.04	.23	1.48	6.80			1	19	21	.08		.01		
120.0	125.0	72857	5.0	.0	****	3.43	.07	1.30	5.16	17.10			1	19	21	.05		.01		
125.0	130.0	72858	5.0	.0	****	3.36	.05	1.88	6.58	11.00			1	19	21	.08		.01		
130.0	135.0	72859	5.0	.0	****	3.44	.02	.26	.53	8.90			1	19	21	.07		.01		
135.0	140.0	72860	5.0	.0	****	3.37	.04	1.88	4.05	21.20			1	18	19	.11		.01		
140.0	145.0	72861	5.0	.0	****	3.44	.03	1.01	1.16	13.70			1	18	19	.08		.01		
145.0	150.0	72862	5.0	.0	****	3.53	.05	.72	.91	8.20			1	18	19	.06		.01		
150.0	155.0	72863	5.0	.0	****	3.27	.04	3.09	3.22	37.70			1	18	19	.08		.01		
155.0	160.0	72864	5.0	.0	****	3.39	.03	.33	1.18	10.30			1	15	17	.08		.01		
160.0	165.0	72865	5.0	.0	****	3.25	.04	1.50	2.78	3.40				15	15	.06		.01		
165.0	170.0	72866	5.0	.0	****	3.22	.06	.67	4.50	15.40				15	15	.08		.01		
170.0	175.0	72867	5.0	.0	****	3.31	.04	.42	1.93	8.90			1	15	17	.03		.01		
175.0	180.0	72868	5.0	.0	****	3.29	.07	1.74	3.21	12.30			2	17	19	.07		.01		
180.0	185.0	72869	5.0	.0	****	3.12	.06	1.87	4.48	21.90			2	17	19	.09		.01		
185.0	190.0	72870	5.0	.0	****	2.87	.04	1.35	2.10	22.60			2	17	19	.06		.01		
190.0	195.0	72871	5.0	.0	****	4.02	.02	6.02	12.60	47.30			2	17	19	.02		.01		
195.0	200.0	72872	5.0	.0	****	4.72	.02	6.05	12.20	51.40			1	36	38	.01		.01		
200.0	205.0	72873	5.0	.0	****	4.76	.01	1.91	6.38	28.80			1	36	38			.01		
205.0	210.0	72874	5.0	.0	****	4.79	.02	1.20	6.25	15.10			1	36	38	.02		.01		
210.0	215.0	72875	5.0	.0	****	4.85	.02	3.53	7.31	32.90			1	36	38	.01		.01		
215.0	220.0	72876	5.0	.0	****	4.67	.03	7.45	17.20	63.80			3	14	17			.04		
220.0	225.0	72877	5.0	.0	****	3.22	.24	.67	5.27	10.30			3	14	17	.05		.04		
225.0	230.0	72878	5.0	.0	****	3.14	.10	.50	2.00	14.40			3	14	17	.04		.04		
230.0	235.0	72879	5.0	.0	****	2.89	.15	.35	.44	8.60			3	14	17	.09		.04		
235.0	240.0	72880	5.0	.0	****	2.84	.09	.76	.82	16.10			3	4	8	.12		.05		
240.0	245.0	72881	5.0	.0	****	2.79	.07	.35	.07	3.40			3	4	8	.08		.05		
245.0	250.0	72882	5.0	.0	****	2.99	.18	.45	2.27	5.10			3	4	8	.06		.05		
250.0	255.0	72883	5.0	.0	****	3.05	.19	1.12	3.70	19.50			3	4	8	.07		.05		
255.0	261.0	72884	6.0	.0	****	3.18	.15	2.52	5.18	39.10			3	4	8	.04		.05		

DDH: 76-01

---DEPTHS---		SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														
FROM	TO					CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
607.4	609.0	73057	1.6	.0	2C9	2.99	.41	1.02	2.72	24.30			6	12	18	.16		.10		
609.0	611.0	73058	2.0	.0	2C9	3.41	.59	.80	.46	27.39			6	12	18	.08		.10		
611.0	613.0	73059	2.0	.0	2D39	3.33	.41	3.49	1.38	52.10			6	12	18	.08		.10		
613.0	614.2	73060	1.2	.0	2D39	3.08	.29	2.02	3.16	21.60			6	12	18	.11		.10		
614.2	614.8	73061	.6	.0	2D3	3.47	.14	1.43	3.58	8.19			6	12	18	.10		.10		
614.8	616.0	73062	1.2	.0	2D3	3.91	.05	8.16	18.10	32.60			6	12	18	.14		.10		
616.0	616.5	73063	.5	.0	2D3	3.75	.17	3.47	2.85	17.80			6	12	18	.05		.10		
616.5	616.8	73064	.3	.0	1E19	2.99	.10	.29	.23	8.19			6	12	18	.35		.10		
616.8	617.2	73065	.4	.0	1E19	2.98	.13	.39	.10	8.90			6	12	18	.22		.10		
617.2	617.4	73066	.2	.0	2D39	4.46	.07	8.65	9.16	39.79			6	12	18	.08		.10		
617.4	618.3	73067	.9	.0	2D3	3.81	.23	8.04	10.90	41.79			6	12	18	.08		.10		
618.3	618.9	73068	.6	.0	2D3	3.54	.13	2.73	4.05	21.19			6	12	18	.08		.10		
618.9	619.6	73069	.7	.0	2C0	3.37	.14	.35	.27	16.39			6	12	18	.08		.10		
619.6	619.9	73070	.3	.0	1D4	2.91	.04	.14	.23				2	16	19	.14		.02		
619.9	621.0	73071	1.1	.0	1D4	2.87	.02	.11	.19				2	16	19	.16		.02		
621.0	621.7	73072	.7	.0	1D4	3.29	.10	.16	.38	7.90			2	16	19	.13		.02		
621.7	623.0	73073	1.3	.0	2C0	3.49	.10	.99	1.96	12.30			2	16	19	.10		.02		
623.0	623.5	73074	.5	.0	2D35	3.47	.04	1.17	3.29	8.59			2	16	19	.13		.02		
623.5	626.4	73075	2.9	.0	2D35	3.47	.05	2.41	3.37	11.59			2	16	19	.11		.02		
626.4	631.4	73076	5.0	.0	2C53	3.62	.11	.99	2.17				2	16	19	.08		.02		
631.4	636.4	73077	5.0	.0	2D35	3.43	.05	1.74	5.96	9.59			2	16	19	.11		.02		
636.4	639.4	73078	3.0	.0	2D35	3.54	.05	1.99	5.94	10.30			2	16	19	.11		.02		
639.4	640.7	73079	1.3	.0	2C35	3.39	.04	.93	2.35				2	16	19	.11		.02		
640.7	645.7	73080	5.0	.0	2D35	3.37	.11	1.37	2.60	15.80			2	20	22	.11		.02		
645.7	650.7	73081	5.0	.0	2C35	3.47	.07	.47	3.20				2	20	22	.13		.02		
650.7	655.7	73082	5.0	.0	2C35	3.68	.10	.61	1.34				2	20	22	.10		.02		
655.7	660.0	73083	4.3	.0	2C3	3.85	.13	.54	1.35	4.79			2	20	22	.05		.02		
660.0	661.0	73084	1.0	.0	2C3	3.87	.08	.08	.69	6.79			2	20	22	.08		.02		
661.0	665.0	73085	4.0	.0	2C3	4.15	.29	.44	1.39	3.39			3	24	27	.05		.02		
665.0	666.0	73086	1.0	.0	2E4	4.33	.17	1.95	5.48				3	24	27	.02		.02		
666.0	669.0	73087	3.0	.0	2C3	3.89	.11	.41	.62	7.49			3	24	27	.05		.02		
669.0	671.0	73088	2.0	.0	2A3C	3.47	.04	1.28	1.60	8.19			3	24	27	.17		.02		

DDH: 76-02

-----DEPTHS-----				-----ASSAYS-----																
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
791.5	792.7	73145	1.2	.0	2E8&	4.05	.13	.75	1.18					5	8	13	.02			.05
792.7	793.4	73146	.7	.0	2D4	3.41	.17	4.26	11.69	26.39				5	8	13	.01			.05
793.4	796.5	73147	3.1	.0	2B0	2.95	.14	.68	.94	58.20				5	8	13	.10			.05
796.5	801.5	73148	5.0	.0	2B0(3.37	.20	5.15	1.63	238.99				5	8	13	.05			.05
801.5	805.5	73149	4.0	.0	2C0(3.06	.13	2.39	5.29	14.40				5	8	13	.10			.05

DDH: 76-03

-----DEPTHS-----				-----ASSAYS-----																
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
766.0	771.0	73205	5.0	.0	2E19	3.79	.32	.17	1.08						.08		.08			
771.0	776.0	73206	5.0	.0	2E19	4.06	.38	.11	.88						.02		.08			
776.0	781.0	73207	5.0	.0	2E19	3.83	.34	.51	1.89						.05		.08			
781.0	784.0	73208	3.0	.0	2F4	4.42	.04	10.27	20.80						.08		.05			
784.0	786.1	73209	2.1	.0	2E0	4.42	.13	.10	1.65						.04		.05			
786.1	788.0	73210	1.9	.0	2F4	4.21	.07	5.12	14.80						.02		.05			
788.0	791.0	73211	3.0	.0	0Q9	2.93	.17	3.04	1.87						.05		.05			
791.0	796.0	73212	5.0	.0	2B0	2.85	.08	.56	1.78						.27		.05			
796.0	798.0	73213	2.0	.0	2B0	2.87	.11	.47	.90						.32		.05			
798.0	801.4	73214	3.4	.0	2B9	3.14	.20	.84	3.00						.13		.05			
801.4	805.0	73215	3.6	.0	2C7&	3.12	.05	.28	1.58						.14		.04			
805.0	806.0	73216	1.0	.0	2D4	3.75	.08	5.28	13.40						.07		.04			
806.0	811.0	73217	5.0	.0	2D0	3.35	.08	2.27	5.79						.08		.04			
811.0	816.0	73218	5.0	.0	2D4	3.70	.11	7.04	17.00						.10		.04			
816.0	821.0	73219	5.0	.0	2D0	3.49	.07	2.48	6.65						.11		.04			
821.0	822.3	73220	1.3	.0	2D0	3.35	.22	2.37	6.28						.11		.04			
822.3	826.0	73221	3.7	.0	2D0	3.02	.13	2.41	2.54						.20		.05			
826.0	831.0	73222	5.0	.0	2C0	2.98	.19	.49	.99						.24		.05			
831.0	836.0	73223	5.0	.0	2B0	2.98	.17	.40	2.50						.23		.05			
836.0	841.5	73224	5.5	.0	2B0	2.87	.10	.66	1.69						.27		.05			

DDH: 76-04

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													
FROM	TO						CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe %	BAO %	Hg %	Mn %	As %	Ba %
628.7	632.0	73230	3.3	.0	2F64	3.89	.34	6.91	6.76	98.00		.14	5	25	30	.16		.16		
632.0	637.0	73231	5.0	.0	2F64	4.41	60.17	5.67	5.50	70.29		.14	5	25	30	15.51		.16		
637.0	642.0	73232	5.0	.0	2E4	4.25	.02	3.08	4.95	36.00		.07	5	25	30	9.69		.16		
642.0	647.0	73233	5.0	.0	2E0	4.38	.11	1.28	2.52	2.70		.07	5	25	30	.02		.16		
647.0	652.0	73234	5.0	.0	2E0	3.79	40.10	.67	.67	15.09			1	27	29	.02				
652.0	657.0	73235	5.0	.0	2E0	3.99	40.04	.08	.26	3.39			1	27	29	.02				
657.0	662.0	73236	5.0	.0	2EC	3.68	.02	.11	.20				1	27	29	.02				
662.0	667.0	73237	5.0	.0	2EC	3.72	.02	.20	.17	11.59			1	27	29	.01				
667.0	672.0	73238	5.0	.0	2EC	3.89	40.02	.24	.20				2	28	30	.02		.02		
672.0	677.0	73239	5.0	.0	2EC	3.72	40.04	.17	.08				2	28	30	.01		.02		
677.0	682.0	73240	5.0	.0	2EC	3.45	.04	.28	.11	13.00			2	28	30	.02		.02		
682.0	687.0	73241	5.0	.0	2E0	4.51	.05	2.08	2.99	15.09		.01	2	28	30	.02		.02		
687.0	692.0	73242	5.0	.0	2E0	3.85	50.05	1.27	.23	45.89		1.99	3	31	35	.01		.02		
692.0	697.0	73243	5.0	.0	2E4	5.34	50.07	3.89	1.30	15.40		.07	3	31	35	.01		.02		
697.0	702.0	73244	5.0	.0	2E4	4.48	.24	2.81	2.73	14.40		.01	3	31	35	.02		.02		
702.0	707.0	73245	5.0	.0	2E0	4.33	40.10	.80	1.35	7.49			3	31	35	.02		.02		
707.0	712.0	73246	5.0	.0	2E0	4.71	40.07	.13	.11	7.90			3	32	35	.10		.02		
712.0	717.0	73247	5.0	.0	2G0	4.74	60.07	4.37	8.75	39.79		.14	3	32	35	25.50		.02		
717.0	722.0	73248	5.0	.0	2H0	4.37	.44	2.37	3.62	21.89		.14	3	32	35	1.32		.02		
722.0	727.0	73249	5.0	.0	2EC	4.15	.04	.28	.26	8.90			3	32	35	.11		.02		
727.0	732.0	73250	5.0	.0	2EC	4.06	40.05	1.50	2.10	4.09		.07	4	27	31	.02		.08		
732.0	737.0	73251	5.0	.0	2EC4	4.02	.14	3.39	4.02	28.80		.07	4	27	31	.08		.08		
737.0	742.0	73252	5.0	.0	2EC	3.70	.23	.69	1.33			.07	4	27	31	.13		.08		
742.0	747.0	73253	5.0	.0	2EC	3.83	40.53	.19	.68	4.79			4	27	31	.02		.08		
747.0	752.0	73254	5.0	.0	1D4	3.31	.27	2.06	2.12	16.39		.21	6	14	21	.02		.17		
752.0	757.0	73255	5.0	.0	2EC	3.74	.23	1.03	1.44	8.19		.14	6	25	31	.02		.17		
757.0	762.0	73256	5.0	.0	2EC	4.08	40.26	.57	1.76	6.50			6	25	31	.05		.17		
762.0	767.0	73257	5.0	.0	2E8	4.51	.45	.57	1.11	6.50			6	25	31	.02		.17		
767.0	772.0	73258	5.0	.0	2EF	4.15	.44	2.41	2.72	12.30		.07	4	27	32	.10		.08		
772.0	777.0	73259	5.0	.0	2F4	4.50	50.08	4.95	10.19	18.80		.07	4	27	32	.02		.08		
777.0	782.0	73260	5.0	.0	2E1	4.09	50.19	1.88	2.27	6.20		.07	4	27	32	.05		.08		
782.0	787.0	73261	5.0	.0	2E14	3.97	.05	2.75	5.41	18.80		.14	4	27	32	.05		.08		
787.0	792.0	73262	5.0	.0	2D0	3.29	.08	2.73	6.95	35.70		1.37	4	12	17	.05		.05		
792.0	797.0	73263	5.0	.0	2C0	3.37	21.05	.49	1.69	19.89		.62	4	12	17	.05		.05		
797.0	802.0	73264	5.0	.0	2D4	3.62	21.04	6.20	13.19	44.60		.21	4	12	17	.07		.05		
802.0	807.0	73265	5.0	.0	2D4	3.74	.08	6.90	16.39	56.89		.27	4	12	17	.11		.05		
807.0	812.0	73266	5.0	.0	2C0	2.89	21.07	1.36	1.66	32.90		.55	4	3	8	.20		.08		
812.0	817.0	73267	5.0	.0	2D0	3.22	.17	3.00	4.70	53.79		1.92	4	3	8	.28		.08		

DDH: 76-05

---DEPTHS---		SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	---ASSAYS---							S.G. W.R.		
FROM	TO											Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %		Ba %	
678.2	680.0	73324	1.8	.0	2C0	3.07	.13	.30	.53			6	26	32	.19		.12				
680.0	683.0	73325	3.0	.0	2C9	3.53	50.25	2.54	1.50	8.20		6	26	32	.13		.12				
683.0	685.0	73326	2.0	.0	2E10	4.78	.13	3.64	6.66	25.40		6	26	32	.05		.12				
685.0	688.0	73327	3.0	.0	2E11	4.45	.15	3.45	5.84	20.60		6	26	32	.04		.12				
688.0	690.0	73328	2.0	.0	2F4	4.80	.06	6.86	12.50	13.00		6	26	32	.05		.12				
690.0	695.0	73329	5.0	.0	2F4	4.79	50.05	4.63	8.83	29.50		6	26	32	.03		.12				
695.0	699.5	73330	4.5	.0	2E41	4.29	.16	2.37	5.28	19.20		5	25	31	.07		.04				
699.5	700.5	73331	1.0	.0	2D5	3.30	.14	3.00	5.37	52.80		5	25	31	.21		.04				
700.5	705.0	73332	4.5	.0	2E41	4.65	.15	4.25	5.81	3.40		5	25	31	.04		.04				
705.0	709.0	73333	4.0	.0	2D08	3.26	.11	1.62	3.32	19.50		5	25	31	.21		.04				
709.0	710.0	73334	1.0	.0	2E13	4.76	.06	.10	.61	13.70		5	25	31	.03		.04				
710.0	712.5	73335	2.5	.0	2E13	4.01	21.14	.44	1.00	13.70		5	25	31	.07		.04				
712.5	715.0	73336	2.5	.0	2D9	3.03	.24	1.98	3.83	13.00		6	5	11	.15		.07				
715.0	720.0	73337	5.0	.0	2C00	3.47	.12	1.65	2.27	19.20		6	5	11	.17		.07				
720.0	725.3	73338	5.3	.0	2B0	2.99	.15	.28	.23	47.30		6	5	11	.15		.07				

DDH: 76-06

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----												
FROM	TO						CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %
628.0	630.1	73395	2.1	.0	2E43	4.65	.38	2.65	4.82	26.40				5	22	28	.04		.16
630.1	633.4	73396	3.3	.0	2F47	4.24	.81	3.62	8.20	34.30				5	22	28	.13		.16
633.4	638.4	73397	5.0	.0	2D9	3.03	.34	.85	4.46	17.50				5	22	28	.41		.16
638.4	640.3	73398	1.9	.0	2D0	3.13	.13	.67	3.38	18.80				5	22	28	.22		.16
640.3	641.0	73399	.7	.0	2E4	4.74	.11	2.12	5.46	20.90				5	22	28	.04		.16
641.0	643.3	73400	2.3	.0	2E49	4.31	.21	2.08	3.90	16.50				5	22	28	.03		.16
643.3	645.2	73401	1.9	.0	2E49	4.27	.25	2.30	4.18	13.00				5	22	28	.03		.16
645.2	650.7	73402	5.5	.0	2E89	4.24	.52	1.44	2.51	14.70				5	22	28	.05		.16
650.7	656.0	73403	5.3	.0	2E89	4.50	.36	1.37	1.64	13.70				4	37	41	.14		.11
656.0	660.0	73404	4.0	.0	2E19	4.02	.41	1.19	1.09	15.80				4	37	41	.03		.11
660.0	660.8	73405	.8	.0	2E8	4.55	.15	.30	.40	9.90				4	37	41	.04		.11
660.8	661.4	73406	.6	.0	2E0	4.61	.10	1.31	2.42	14.70				4	37	41	.05		.11
661.4	662.2	73407	.8	.0	2E9	4.67	.21	.53	.81	14.70				4	37	41	.11		.11
662.2	662.5	73408	.3	.0	2E4	4.50	.17	1.64	3.21	14.40				4	37	41	.03		.11
662.5	667.5	73409	5.0	.0	2E89	4.42	.36	.30	.78	13.40				4	37	41	.04		.11
667.5	671.3	73410	3.8	.0	2E9	4.55	.39	.30	1.30	14.40				6	28	34	.11		.11
671.3	675.9	73411	4.6	.0	2F1	4.29	.21	2.00	4.40	17.50				6	28	34	.06		.11
675.9	677.0	73412	1.1	.0	2F1	3.48	.36	5.00	3.44	40.80				6	28	34	.19		.11
677.0	678.0	73413	1.0	.0	2E4&	4.67	.19	1.85	3.80	18.20				6	28	34	.05		.11
678.0	680.5	73414	2.5	.0	2E4	4.44	.05	4.33	4.33	27.80				6	28	34	.07		.11
680.5	681.0	73415	.5	.0	2E1	4.72	.04	.87	.87	13.70				6	28	34	.06		.11
681.0	682.0	73416	1.0	.0	2E1	4.27	.06	1.21	1.21	14.40				6	28	34	.03		.11
682.0	685.2	73417	3.2	.0	2E1	5.81	.08	1.75	1.75	20.20				6	28	34	.09		.11
685.2	689.1	73418	3.9	.0	2H43	3.48	.41	4.00	7.83	29.10				6	28	34	.04		.11
689.1	692.0	73419	2.9	.0	2D39	2.91	.81	.61	3.95	85.40				7	7	14	.18		.05
692.0	696.0	73420	4.0	.0	2A4	3.11	.17	1.78	4.60	30.20				7	7	14	.15		.05
696.0	700.0	73421	4.0	.0	2A4	3.04	.34	3.40	3.72	54.20				7	7	14	.19		.05
700.0	704.5	73422	4.5	.0	2A0	2.96	.17	1.30	2.42	27.80				7	7	14	.25		.05
704.5	705.7	73423	1.2	.0	2A0	2.88	.05	1.72	2.03	38.10				7	7	14	.17		.05
705.7	707.7	73424	2.0	.0	2A0	2.75	.05	.79	2.70	17.10				7	7	14	.18		.05
707.7	712.7	73425	5.0	.0	2A4	2.75	.04	1.12	3.92	30.50				3	7	10	.15		.03
712.7	717.7	73426	5.0	.0	2A4	2.62	.09	.90	3.20	34.30				3	7	10	.16		.03
717.7	719.7	73427	2.0	.0	2A0	2.76	.14	.18	.15	14.70				3	7	10	.18		.03
719.7	723.2	73428	3.5	.0	2A0	2.54	.11	.13	.18	15.80				3	7	10	.19		.03
723.2	723.7	73429	.5	.0	2A0	3.44	.23	.14	.30	20.20				3	7	10	.09		.03
723.7	727.0	73430	3.3	.0	2A0	2.42	.05	.95	1.61	63.80				3	7	10	.28		.03
727.0	727.9	73431	.9	.0	0Q9	2.72	.30	1.02	.37	93.60				5	8	14	.05		.02
727.9	730.0	73432	2.1	.0	2B4	2.92	.13	4.35	3.60	154.30				5	8	14	.04		.02
730.0	731.8	73433	1.8	.0	2D5	2.92	.13	4.35	3.60	154.30				5	8	14	.05		.02
731.8	736.8	73434	5.0	.0	2D5	2.86	.15	1.68	5.55	44.60				5	8	14	.20		.02
736.8	741.8	73435	5.0	.0	2D5	2.88	.15	2.24	2.90	175.20				5	8	14	.15		.02
741.8	746.8	73436	5.0	.0	2D5	3.03	.12	2.81	4.74	50.10				5	8	14	.23		.02
746.8	750.5	73437	3.7	.0	2D79	3.22	.42	1.64	4.43	26.40				5	8	14	.14		.02
750.5	755.0	73438	4.5	.0	2D79	3.07	.27	2.00	6.45	32.90				8	3	11	.13		.04
755.0	756.3	73439	1.3	.0	2D5	2.99	.13	4.80	8.91	48.00				8	3	11	.16		.04
756.3	761.3	73440	5.0	.0	2A41	2.72	.06	3.30	4.50	55.20				8	3	11	.22		.04
761.3	766.3	73441	5.0	.0	2A4	3.22	.12	1.60	4.45	35.70				8	3	11	.15		.04
766.3	771.3	73442	5.0	.0	2A0	2.46	.11	.33	1.90	8.20				8	3	11	.16		.04

DDH: 76-07

---DEPTHS---				-----ASSAYS-----																
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. FULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
670.0	675.0	73499	5.0	.0	1D4	2.79	.03	.05	.08					3	1	5	.25			.06
675.0	680.0	73500	5.0	.0	1D4	2.72	.02	.07	.14					3	1	5	.18			.06
680.0	685.0	73501	5.0	.0	1D4	2.72	.01	.09	.12	8.90				3	1	5	.18			.06
685.0	685.6	73502	.6	.0	2A4	2.77	.03	1.83	3.40	31.90				3	1	5	.15			.06
685.6	686.2	73503	.6	.0	1D4	2.67	.04	.09	.59	3.10				3	1	5	.30			.06
686.2	688.2	73504	2.0	.0	2A4	2.83	.04	1.64	2.82	22.30				3	1	5	.20			.06
688.2	690.5	73505	2.3	.0	1D4	2.76	.10	.45	.36	22.30				3	1	5	.88			.06
690.5	691.9	73506	1.4	.0	2A0	2.87	.08	.97	2.77	31.90				3	1	5	.15			.06

DDH: 76-08

---DEPTHS---				-----ASSAYS-----																
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
604.0	607.0	73565	3.0	.0	2E49	4.76	3.59	6.20	1.40					17	23	41	.04			.10
607.0	609.7	73566	2.7	.0	2H43	4.10	4.48	4.34	45.30					17	23	41	.03			.10
609.7	614.7	73567	5.0	.0	2H43	3.88	5.04	5.92	47.30					17	23	41	.07			.10
614.7	619.7	73568	5.0	.0	2H43	3.68	3.56	3.71	25.40					25	11	37	.03			.09
619.7	624.7	73569	5.0	.0	2H43	4.29	4.48	5.90	56.90					25	11	37	.04			.09
624.7	629.7	73570	5.0	.0	2H43	3.76	2.18	4.96	53.50					25	11	37	.13			.09
629.7	632.7	73571	3.0	.0	2D43	3.53	4.97	10.80	66.50					25	11	37	.07			.09
632.7	635.2	73572	2.5	.0	2D37	3.33	1.10	4.25	24.00					2	3	6	.17			.04
635.2	640.0	73573	4.8	.0	2A0	3.09	.90	2.39	24.70					2	3	6	.19			.04
640.0	645.0	73574	5.0	.0	2A0	2.59	.93	2.25	25.40					2	3	6	.18			.04
645.0	650.0	73575	5.0	.0	2A0	2.91	1.35	2.29	17.80					2	3	6	.15			.04
650.0	655.0	73576	5.0	.0	2A4	2.97	2.00	3.98	31.50					2	3	6	.16			.04

177.6
 3.70 , 4.37
 8.47

DDH: 76-09

-----DEPTHS-----				-----ASSAYS-----																
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
496.2	500.0	73581	3.8	.0	1D49	3.38	Waste	3.16	2.80	47.00		20	9	30	.21		.21			
500.0	500.7	73582	.7	.0	2H43	4.22	1.36	6.53	6.18	133.00		20	9	30	.06		.21			
500.7	504.0	73583	3.3	.0	2H43	4.50	.80	4.54	4.82	49.40		20	9	30	.03		.21			
504.0	506.5	73584	2.5	.0	2E49	4.81	.26	4.32	6.06	47.30		7	24	32	.03		.20			
506.5	508.0	73585	1.5	.0	2E41	4.88	.15	4.18	3.77	30.90		7	24	32	.05		.20			
508.0	511.0	73586	3.0	.0	0Q9	3.94	50.30	5.68	5.23	61.70		7	24	32	.13		.20			
511.0	514.0	73587	3.0	.0	2E41	3.89	.25	3.54	6.35	49.40		7	24	32	.07		.20			
514.0	518.4	73588	4.4	.0	2E49	4.74	.20	5.04	5.80	41.10		7	24	32	.11		.20			
518.4	519.7	73589	1.3	.0	2E41	4.22	.43	5.02	4.68	66.50		7	24	32	.10		.20			
519.7	520.3	73590	.6	.0	2E41	4.10	.17	5.44	9.58	75.40		7	24	32	.22		.20			
520.3	521.3	73591	1.0	.0	2E46	4.63	.31	4.68	5.38	64.40		7	24	32	5.18		.20			
521.3	522.5	73592	1.2	.0	2E46	4.65	.18	5.09	6.20	65.10		7	24	32	6.91		.20			
522.5	522.8	73593	.3	.0	2E46	4.35	.49	4.00	5.00	54.90		7	24	32	.16		.20			
522.8	524.1	73594	1.3	.0	2E46	4.72	60.09	7.55	8.86	236.60		7	24	32	.09		.20			
524.1	525.9	73595	1.8	.0	2E46	4.57	.15	4.67	5.01	61.70		9	24	34	7.70		.36			
525.9	527.2	73596	1.3	.0	2E46	4.55	.28	5.35	5.40	76.80		9	24	34	1.46		.36			
527.2	528.5	73597	1.3	.0	2E46	4.59	.24	5.02	6.00	84.30		9	24	34	.87		.36			
528.5	530.7	73598	2.2	.0	2E41	4.61	.24	5.48	5.68	68.60		9	24	34	5.59		.36			
530.7	535.7	73599	5.0	.0	2E41	4.63	.28	5.00	5.39	73.40		9	24	34	4.47		.36			
535.7	540.7	73600	5.0	.0	2E41	4.57	.17	6.10	5.80	93.90		9	24	34	3.81		.36			
540.7	542.7	73601	2.0	.0	2H43	3.97	.24	5.43	6.66	98.70		9	24	34	.66		.36			
542.7	545.0	73602	2.3	.0	2D4	3.17	.13	2.62	7.86	35.30		7	2	9	.15		.08			
545.0	550.0	73603	5.0	.0	2D0	3.13	.17	1.36	3.44	33.30		7	2	9	.22		.08			
550.0	551.5	73604	1.5	.0	2D9	3.23	21.22	2.18	6.58	15.80		7	2	9	.33		.08			
551.5	553.2	73605	1.7	.0	2B4	3.00	.14	1.68	3.00	52.50		7	2	9	.31		.08			
553.2	556.5	73606	3.3	.0	2A9	2.94	.22	1.10	1.86	18.50		7	2	9	.35		.08			
556.5	561.5	73607	5.0	.0	2A0	2.75	.06	.45	1.28	13.40		7	2	9	.42		.08			
561.5	566.5	73608	5.0	.0	2A0	2.65	.05	.48	.94	20.90		4	1	5	.46		.03			
566.5	571.5	73609	5.0	.0	2A0	2.74	.05	.55	.96	5.80		4	1	5	.50		.03			
571.5	571.9	73610	.4	.0	1D09	2.71	.13	.53	1.33	27.80		4	1	5	.49		.03			
571.9	573.0	73611	1.1	.0	1D09	2.79	.08	.16	.25	31.90		4	1	5	.86		.03			
573.0	574.3	73612	1.3	.0	2A9	2.72	21.99	.59	.82	20.60		4	1	5	.37		.03			
574.3	575.6	73613	1.3	.0	2A0	2.70	.07	.52	.97	17.80		4	1	5	.38		.03			
575.6	577.1	73614	1.5	.0	2A0	2.67	.05	1.16	1.13	39.80		4	1	5	.36		.03			
577.1	580.5	73615	3.4	.0	2A0	2.67	.05	1.26	1.40	43.20		4	1	5	.40		.03			
580.5	585.5	73616	5.0	.0	2B0	2.79	.05	1.15	1.16	39.40		4	1	5	.39		.03			
585.5	589.0	73617	3.5	.0	2A0	2.81	.09	3.08	.91	105.60		3	3	7	.35		.03			
589.0	593.8	73618	4.8	.0	2B0	2.81	21.08	2.52	1.22	86.40		3	3	7	.38		.03			
593.8	596.4	73619	2.6	.0	2A0	2.76	.04	.80	.93	27.40		3	3	7	.31		.03			
596.4	601.4	73620	5.0	.0	2A0	2.62	.07	.60	1.09	20.60		3	3	7	.33		.03			

55.31
0.27, 4.46, 5.43, 6.30g

DDH: 76-10

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----												
FROM	TO						CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %
521.5	524.2	73626	2.7	.0	2C0&	3.34	.14	.40	.95	2.10				7	18	26	.06		.05
524.2	529.2	73627	5.0	.0	2D01	3.04	23.11	1.50	3.40	18.50				7	18	26	.18		.05
529.2	530.5	73628	1.3	.0	2H43	4.57	.27	6.63	9.25	94.60				7	18	26	.37		.05
530.5	531.3	73629	.8	.0	2H43	4.29	.36	3.80	5.88	23.30				7	18	26	.05		.05
531.3	534.0	73630	2.7	.0	2H43	4.59	70.21	8.50	12.40	36.00				7	18	26	.06		.05
534.0	537.0	73631	3.0	.0	2H43	4.50	.06	5.34	8.25	34.30				7	18	26	.07		.05
537.0	538.0	73632	1.0	.0	2D4	4.46	.10	4.54	7.65	42.50				3	4	7	.11		.04
538.0	542.0	73633	4.0	.0	2C0	2.97	.18	.80	2.50	18.50				3	4	7	.27		.04
542.0	545.0	73634	3.0	.0	2C0	2.84	21.14	1.08	1.37	53.40				3	4	7	.24		.04
545.0	550.0	73635	5.0	.0	2A0	2.91	.08	.91	1.89	24.70				3	4	7	.22		.04
550.0	555.0	73636	5.0	.0	2A4	2.91	.04	1.97	4.42	21.20				3	4	7	.36		.04
555.0	560.0	73637	5.0	.0	2A0	2.92	.06	.85	.95	10.30				3	4	7	.37		.04

13.8

.05 4.54 7.22 34.54

DDH: 76-11

					-----ASSAYS-----															
---DEPTHS---	SAMPLE	INT.	REC.	ROCK	S.G.	CU	Pb	Zn	Ag(AA)	Ag(FA)	Au(FA)	Po	Py	TOT	BAO	Hg	Mn	As	Ba	S.G.
FROM	TO	NO.		UNIT	PULP	%	%	%	g/mT	g/mT	g/mT	%	%	Fe	%	%	%	%	%	W.R.
501.0	506.0	73643	5.0	.0	2B45	3.09	.05	3.48	5.48	38.70				4	8	13	.37			.07
506.0	511.0	73644	5.0	.0	0Q9	2.92	23.03	2.28	5.33	30.50				4	8	13	.23			.07
511.0	516.0	73645	5.0	.0	2B45	2.96	.05	1.80	3.85	26.40				4	8	13	.32			.07
516.0	521.0	73646	5.0	.0	2E42	4.62	.12	4.90	7.90	56.90				4	8	13	.11			.07
521.0	526.0	73647	5.0	.0	2E42	3.73	70.17	4.60	6.58	65.80				7	8	15	.06			.18
526.0	531.0	73648	5.0	.0	0Q9	2.90	.03	5.33	2.20	90.90				7	8	15	.16			.18
531.0	536.0	73649	5.0	.0	2J41	3.76	.25	11.90	13.50	310.00				7	8	15	.29			.18
536.0	541.0	73650	5.0	.0	2J41	4.00	70.27	12.30	16.60	384.00				7	8	15	.17			.18
541.0	544.0	73651	3.0	.0	2J4	3.26	.11	6.85	8.88	132.40				7	8	15	.24			.18

43

.17 5.90 7.76

DDH: 76-12

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----											S.G. W.R.	
FROM	TO						CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %		Mn %
535.8	536.2	73656	.4	.0	2E4	4.27	.06	5.10	6.22	107.00			4	30	34	.02			.19
536.2	536.9	73657	.7	.0	1F4	2.87 ⁵⁰	.18	.90	.33	19.90			4	30	34	.02			.19
536.9	542.5	73658	5.6	.0	2E4	4.56	.17	5.36	3.50	109.70			4	30	34	.02			.19
542.5	547.5	73659	5.0	.0	2C0	4.04	.03	.20	.13	7.20			1	32	34	.02			.16
547.5	552.6	73660	5.1	.0	2C0	3.76	.03	.81	.76	11.60			1	32	34	.02			.16
552.6	556.0	73661	3.4	.0	2E49	4.68 ⁴⁰	.27	2.24	2.27	27.40			1	32	34	.02			.16
556.0	561.0	73662	5.0	.0	2C0	3.95	.09	1.08	.21	16.10			1	32	34	.02			.16
561.0	566.0	73663	5.0	.0	2C0	4.04	.02	.20	.11	6.50			1	37	38	.01			.04
566.0	566.7	73664	.7	.0	2E0	4.38	.08	.45	.25	9.20			1	37	38	.03			.04
566.7	568.2	73665	1.5	.0	2C0	4.32 ⁴⁰	.08	.61	.20	10.60			1	37	38	.03			.04
568.2	576.0	73666	7.8	.0	2E0	4.32	.07	.61	.45	15.80			1	37	38	.03			.04
576.0	581.2	73667	5.2	.0	2E41	4.73 ⁵⁰	.10	2.85	3.52	27.40			1	37	38	2.51			.04
581.2	586.4	73668	5.2	.0	2E46	4.82	.03	2.05	4.50	18.80			2	36	38	8.28			.09
586.4	590.1	73669	3.7	.0	2E41	4.55 ⁶⁰	.33	2.40	3.18	29.50			2	36	38	2.81			.09
590.1	591.0	73670	.9	.0	2E48	4.50	.38	4.44	3.33	54.20			2	36	38	.08			.09
591.0	593.2	73671	2.2	.0	2C9	4.46	.27	.77	.32	21.60			2	36	38	.07			.09
593.2	593.7	73672	.5	.0	2F0	4.86	.16	3.26	3.60	39.10			2	36	38	.06			.09
593.7	595.0	73673	1.3	.0	2C0	4.60	.08	.74	.61	13.70			2	36	38	.01			.09
595.0	599.2	73674	4.2	.0	2C0	4.16	.09	.54	.44	56.20			2	36	38	.01			.09
599.2	600.0	73675	.8	.0	2F9	4.64 ⁵⁰	.24	5.42	3.79	16.10			2	36	38	.02			.09
600.0	600.7	73676	.7	.0	2C0	4.85	.06	.92	.46	12.00			2	36	38	.01			.09
600.7	601.6	73677	.9	.0	2E9	4.54	.28	1.95	1.93	26.40			2	36	38	.02			.09
601.6	602.4	73678	.8	.0	2E89	4.24	.30	1.37	1.96	25.70			2	36	38	.02			.09
602.4	606.7	73679	4.3	.0	2E49	4.23	.34	1.38	2.90	21.60			4	28	33	.01			.20
606.7	610.0	73680	3.3	.0	2E9	4.41	.24	1.27	1.68	17.10			4	28	33	.02			.20
610.0	613.0	73681	3.0	.0	2E49	4.92	.24	4.25	1.13	29.80			4	28	33	.02			.20
613.0	619.0	73682	6.0	.0	2D0	3.67	.10	1.31	3.61	16.80			4	28	33	.08			.20
619.0	623.0	73683	4.0	.0	2D0	3.72	.06	.90	6.35	20.20			4	28	33	.05			.20
623.0	626.0	73684	3.0	.0	2D0	3.21	.14	1.63	5.21	31.50			3	27	31	.07			.27
626.0	627.0	73685	1.0	.0	2D0	3.31	.12	.83	6.37	31.50			3	27	31	.05			.27
627.0	631.0	73686	4.0	.0	2D35	3.71 ⁵⁰	.07	1.57	6.95	28.80			3	27	31	.10			.27
631.0	632.4	73687	1.4	.0	2E0	4.71	.03	2.46	1.04	21.20			3	27	31	.03			.27
632.4	634.6	73688	2.2	.0	2C9	4.58	.22	.74	.80	19.90			3	27	31	.03			.27
634.6	635.8	73689	1.2	.0	2E48	4.20	.31	4.84	2.66	40.80			3	27	31	.12			.27
635.8	638.0	73690	2.2	.0	2C9	4.40	.42	.90	.82	19.20			3	27	31	.02			.27
638.0	641.7	73691	3.7	.0	2C9	4.24	.28	1.04	2.14	20.90			3	27	31	.01			.27
641.7	644.3	73692	2.6	.0	2E89	4.19	.35	1.19	1.76	19.50			3	27	31	.02			.27
644.3	645.3	73693	1.0	.0	2E9	4.20 ⁴⁰	.33	.56	1.19	15.10			9	29	38	.02			.41
645.3	648.0	73694	2.7	.0	2E48	4.39	.22	2.60	2.70	21.90			9	29	38	.02			.41
648.0	651.1	73695	3.1	.0	2E89	4.26	.33	1.24	2.55	19.50			9	29	38	.01			.41
651.1	654.5	73696	3.4	.0	2E39	4.62	.28	.90	1.77	10.30			9	29	38	.02			.41
654.5	655.0	73697	.5	.0	2E9	3.18	.22	.72	1.30	13.00			9	29	38	.14			.41
655.0	657.0	73698	2.0	.0	2E39	4.22	.31	.37	.88	9.90			9	29	38	.01			.41
657.0	658.2	73699	1.2	.0	1D41	3.70	.65	.92	1.41	20.90			9	29	38	.05			.41
658.2	660.0	73700	1.8	.0	2C9	4.20	.37	.19	.72	18.50			9	29	38	.03			.41
660.0	664.0	73701	4.0	.0	2C9	5.04 ⁴⁰	.41	.90	1.80	9.60			9	29	38	.01			.41
664.0	665.0	73702	1.0	.0	2F4	5.10	.06	3.50	8.52	11.60			4	30	34	.02			.19
665.0	670.0	73703	5.0	.0	2E89	4.09	.23	1.36	2.15	8.20			4	30	34	.01			.19
670.0	672.0	73704	2.0	.0	2E8	4.47	.17	.73	1.90	8.20			4	30	34	.10			.19
672.0	675.0	73705	3.0	.0	2F4	4.71	.12	4.19	9.60	18.50			4	30	34	.02			.19
675.0	677.0	73706	2.0	.0	2E4	4.42	.06	1.33	5.87	8.90			4	30	34	.03			.19

DDH: 76-12

---DEPTHS---				-----ASSAYS-----																
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
677.0	681.8	73707	4.8	.0	2F4	4.50	.09	5.90	14.40	20.20				4	30	34	.02			.19
681.8	682.4	73708	.6	.0	2F4	4.06	.05	2.82	8.43	12.30				4	30	34	.01			.19
682.4	684.0	73709	1.6	.0	2F4	4.41	.13	6.76	10.10	19.20				4	30	34	.02			.19
684.0	685.7	73710	1.7	.0	2F4	4.54	.28	7.53	11.40	22.60				4	24	28	.04			.29
685.7	690.0	73711	4.3	.0	2E48	3.77	.54	1.27	3.20	12.70				4	24	28	.01			.29
690.0	692.5	73712	2.5	.0	2F4	4.36	.15	4.66	8.15	21.90				4	24	28	.01			.29
692.5	694.6	73713	2.1	.0	2H42	3.96	.13	4.38	8.57	55.20				4	24	28	.02			.29
694.6	696.9	73714	2.3	.0	2F4	4.64	.02	6.50	12.80	51.40				4	24	28	.05			.29
696.9	702.0	73715	5.1	.0	2E41	3.76	.07	1.45	3.43	22.60				4	24	28	.04			.29
702.0	707.0	73716	5.0	.0	2E10	3.68	.16	.51	2.45	9.60				4	24	28	.03			.29
707.0	712.0	73717	5.0	.0	2E41	3.76	.17	3.50	1.25	96.30				2	18	20	.03			.15
712.0	717.0	73718	5.0	.0	2E41	3.46	.07	2.08	3.02	25.40				2	18	20	.03			.15
717.0	722.0	73719	5.0	.0	2E41	3.59	.05	2.49	5.12	21.90				2	18	20	.04			.15
722.0	727.0	73720	5.0	.0	2A40	3.64	.05	2.30	7.55	26.70				2	18	20	.05			.15
727.0	732.0	73721	5.0	.0	2A40	3.43	.06	4.63	10.90	31.90				2	13	15	.04			.14
732.0	737.0	73722	5.0	.0	2A40	3.22	.09	3.10	7.25	24.30				2	13	15	.05			.14
737.0	739.8	73723	2.8	.0	2A40	3.32	.05	1.02	3.18	14.10				2	13	15	.06			.14
739.8	744.8	73724	5.0	.0	2A40	3.49	.09	1.55	6.21	17.80				2	13	15	.05			.14
744.8	749.8	73725	5.0	.0	2A40	3.43	.05	3.97	11.40	25.40				3	6	10	.10			.13
749.8	754.8	73726	5.0	.0	2A40	3.33	.05	6.45	15.00	38.40				3	6	10	.10			.13
754.8	755.7	73727	.9	.0	2E41	3.96	.13	8.35	18.50	47.70				3	6	10	.04			.13
755.7	756.3	73728	.6	.0	2B43	3.62	.16	8.55	8.95	66.20				3	6	10	.05			.13
756.3	758.0	73729	1.7	.0	2D08	2.95	.07	2.82	2.77	68.20				3	6	10	.10			.13

DDH: 76-13

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	-----ASSAYS-----						S.G. W.R.	
FROM	TO												Po %	Py %	TOT Fe	BAO %	Hg %	Mn %		As %
481.5	486.5	73735	5.0	.0	2E01	3.25	.17	.18	1.29	17.20			3	13	17	.05				.03
486.5	490.3	73736	3.8	.0	2C0	3.04	33.20	.62	3.05	32.20			3	13	17	.07				.03
490.3	494.2	73737	3.9	.0	2D05	3.28	.05	1.00	7.48	22.60			3	13	17	.08				.03
494.2	499.2	73738	5.0	.0	2G42	4.65	.17	5.80	5.91	85.40			6	23	29	12.87				.30
499.2	504.2	73739	5.0	.0	2G42	4.63	60.12	4.97	5.82	73.00			6	23	29	13.74				.30
504.2	509.2	73740	5.0	.0	2G42	4.55	60.11	5.22	5.32	84.00			6	23	29	22.42				.30
509.2	514.0	73741	4.8	.0	2G42	4.37	60.34	4.40	4.90	80.20			6	23	29	7.30				.30
514.0	519.0	73742	5.0	.0	2E4&	4.42	60.08	3.07	2.71	57.30			5	11	16	.33				.24
519.0	524.0	73743	5.0	.0	2D0>	3.38	.22	3.62	4.16	69.60			5	11	16	5.24				.24
524.0	529.0	73744	5.0	.0	2A4	2.92	22.04	2.27	4.53	47.70			5	11	16	.37				.24
529.0	534.0	73745	5.0	.0	2A4	2.90	22.04	1.30	3.98	36.30			5	11	16	.44				.24
534.0	539.0	73746	5.0	.0	2A4	2.85	.04	1.79	3.78	43.60			5	5	11	.98				.13
539.0	544.0	73747	5.0	.0	2A4	2.79	22.03	1.21	2.92	35.30			5	5	11	.61				.13
544.0	549.0	73748	5.0	.0	2A4	3.11	22.10	1.94	5.54	47.30			5	5	11	.88				.13
549.0	554.0	73749	5.0	.0	2G4	4.08	.28	7.63	5.87	147.40			5	5	11	10.53				.13
554.0	559.0	73750	5.0	.0	2G42	4.57	60.17	5.51	7.20	112.10			6	21	27	28.32				.10
559.0	564.0	73751	5.0	.0	2F46	4.42	60.12	5.49	8.80	90.50			6	21	27	5.55				.10
564.0	569.0	73752	5.0	.0	2G4	4.57	.08	5.86	7.70	75.10			6	21	27	26.56				.10
569.0	574.0	73753	5.0	.0	2F4	4.78	.05	6.78	11.70	63.80			6	21	27	.49				.10
574.0	579.0	73754	5.0	.0	2F0	4.31	.23	3.00	3.90	31.20			5	34	40	.37				.17
579.0	584.0	73755	5.0	.0	2E8	4.50	50.18	1.60	2.57	20.20			5	34	40	.07				.17
584.0	589.0	73756	5.0	.0	2E8	4.10	.26	1.78	2.46	17.10			5	34	40	.06				.17
589.0	594.0	73757	5.0	.0	2E8	4.52	.19	1.81	4.00	14.40			5	34	40	.05				.17
594.0	599.0	73758	5.0	.0	2E8	4.60	.59	1.73	2.86	23.00			4	35	39	.07				.08
599.0	604.0	73759	5.0	.0	2F0	4.72	50.22	5.08	4.30	24.00			4	35	39	.04				.08
604.0	609.0	73760	5.0	.0	2F0	4.86	.31	2.68	4.53	21.60			4	35	39	.37				.08
609.0	614.0	73761	5.0	.0	2F0	4.50	.15	3.88	5.89	30.20			4	35	39	.09				.08
614.0	619.0	73762	5.0	.0	2F0	4.75	.13	3.85	5.52	29.80			5	27	32	.06				.03
619.0	624.0	73763	5.0	.0	2F0	4.81	50.08	3.95	5.39	23.70			5	27	32	.06				.03
624.0	629.0	73764	5.0	.0	2F0	4.70	.11	3.46	6.25	28.80			5	27	32	.10				.03
629.0	634.0	73765	5.0	.0	2A0	3.02	.08	.73	2.62	19.90			5	27	32	.18				.03
634.0	639.0	73766	5.0	.0	2A0	2.81	21.05	1.18	1.81	36.70			2	4	6	.19				.02
639.0	644.0	73767	5.0	.0	2A0	2.85	21.09	.88	2.29	25.70			2	4	6	.19				.02
644.0	649.0	73768	5.0	.0	2A4	2.81	.07	1.30	3.26	26.10			2	4	6	.24				.02
649.0	654.0	73769	5.0	.0	2A0	2.70	21.04	.79	2.27	9.30			2	4	6	.20				.02
654.0	659.0	73770	5.0	.0	2A4	2.82	21.03	1.30	3.28	18.20			3	1	5	.17				.03
659.0	660.5	73771	1.5	.0	2B4	3.00	.10	1.56	4.27	25.70			3	1	5	.09				.03

DDH: 76-14

-----DEPTHS-----					-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
444.0	449.0	73777	5.0	0	2G48	4.09	60.19	4.11	6.52	76.10				16	16	32	5.10			.22
449.0	454.0	73778	5.0	0	2H4	4.20	70.17	5.00	7.90	85.70				16	16	32	6.17			.22
454.0	459.0	73779	5.0	0	2G4	3.67	60.15	2.73	3.24	48.00				9	10	19	5.45			.22
459.0	464.0	73780	5.0	0	2L2	3.06	Waste	1.08	1.02	15.10				9	10	19	4.71			.22
464.0	469.0	73781	5.0	0	2E46	3.90	60.17	7.58	8.78	103.90				9	10	19	2.93			.22
469.0	474.0	73782	5.0	0	1D4	3.09	Waste	1.68	1.95	49.40				9	10	19	2.54			.22
474.0	479.0	73783	5.0	0	1D4	2.96	70.21	2.88	1.23	93.90				4	25	30	.35			.14
479.0	484.0	73784	5.0	0	2E0	4.20	.21	2.93	1.50	30.50				4	25	30	.08			.14
484.0	489.0	73785	5.0	0	2E4	4.47	50.14	2.75	3.05	17.80				4	25	30	2.33			.14
489.0	494.0	73786	5.0	0	2F4	4.48	.21	4.38	5.85	34.30				4	25	30	.05			.14
494.0	499.0	73787	5.0	0	2E0	4.66	.44	1.60	1.54	32.90				15	23	39	.07			.27
499.0	504.0	73788	5.0	0	2E0	4.26	.27	1.51	1.57	24.30				15	23	39	.08			.27
504.0	509.0	73789	5.0	0	2E81	3.92	40.22	1.77	1.30	21.90				15	23	39	.06			.27
509.0	514.0	73790	5.0	0	2E81	3.83	.16	2.02	1.40	24.70				15	23	39	.07			.27
514.0	519.0	73791	5.0	0	2E0	4.31	.17	2.10	2.00	22.60				7	31	38	.07			.23
519.0	524.0	73792	5.0	0	2E0	4.36	50.19	2.38	2.37	18.80				7	31	38	.10			.23
524.0	529.0	73793	5.0	0	2E8	4.62	.26	2.10	2.42	20.90				7	31	38	.03			.23
529.0	534.0	73794	5.0	0	2E8	4.34	.27	4.12	4.84	38.10				7	31	38	.10			.23
534.0	539.0	73795	5.0	0	2E0	4.61	.21	3.13	2.51	24.30				3	35	39	.04			.09
539.0	544.0	73796	5.0	0	2E0	4.82	.36	1.05	3.46	10.60				3	35	39	.04			.09
544.0	549.0	73797	5.0	0	2F0	4.51	50.20	3.26	5.20	11.60				3	35	39	.03			.09
549.0	554.0	73798	5.0	0	2F0	4.98	.16	1.49	4.96	11.60				3	35	39	.04			.09
554.0	559.0	73799	5.0	0	2F0	4.73	.16	2.90	4.83	17.80				4	30	34	.04			.05
559.0	564.0	73800	5.0	0	2E46	4.58	50.15	3.10	6.30	14.00				4	30	34	.28			.05
564.0	569.0	73801	5.0	0	2D5	3.60	.13	2.66	4.95	18.90				4	30	34	.04			.05

DDH: 76-22

---DEPTHS---				-----ASSAYS-----																
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
504.0	509.0	73807	5.0	.0	2B49	3.71	33.22	3.80	3.50	31.90				5	14	19	.07			.11
509.0	514.0	73808	5.0	.0	2F4	3.77	.13	4.30	5.80	37.00				5	14	19	.07			.11
514.0	519.0	73809	5.0	.0	2E46	3.26	60.35	2.60	4.30	26.10				5	14	19	7.09			.11
519.0	524.0	73810	5.0	.0	2G42	3.80	.13	7.50	8.50	49.00				5	14	19	7.91			.11
524.0	529.0	73811	5.0	.0	2F4	4.04	50.04	7.00	8.30	41.10				4	31	35	.02			.06
529.0	532.4	73812	3.4	.0	2F4	5.08	.31	4.80	6.11	33.20				4	31	35	.14			.06
548.0	553.0	73814	5.0	.0	2H49	4.33	.53	7.00	9.30	58.30				28	12	40	.02			.06
553.0	558.0	73815	5.0	.0	2H49	4.57	70.61	4.90	6.50	40.50				28	12	40	.07			.06
558.0	563.0	73816	5.0	.0	2H49	4.49	.32	7.60	8.40	58.60				28	12	40	.02			.06
563.0	568.0	73817	5.0	.0	2F49	4.81	.36	5.30	7.50	42.50				3	33	37	.03			.04
568.0	573.0	73818	5.0	.0	2F4	4.58	50.10	6.70	8.30	54.90				3	33	37				.04
573.0	578.0	73819	5.0	.0	2F4	4.69	.13	6.50	9.90	49.00				3	33	37	.01			.04
578.0	583.0	73820	5.0	.0	2F4	4.76	.22	4.70	7.00	39.10				3	33	37	.01			.04
583.0	588.0	73821	5.0	.0	2F4	4.84	50.11	5.00	5.70	54.50				9	25	34	.04			.10
588.0	593.0	73822	5.0	.0	2E48	4.70	.20	4.00	3.30	68.60				9	25	34	.14			.10
593.0	598.0	73823	5.0	.0	2H49	4.54	70.32	4.70	7.80	61.00				9	25	34	.11			.10
598.0	603.0	73824	5.0	.0	2D0	3.43	.18	2.40	6.30	44.60				9	25	34	.10			.10
603.0	608.0	73825	5.0	.0	2D0	2.89	21.08	1.50	3.90	26.40				4	2	6	.15			.04
608.0	613.0	73826	5.0	.0	2A4	2.71	.10	2.50	3.20	48.70				4	2	6	.15			.04
613.0	618.0	73827	5.0	.0	1D21	2.74	.06	.08	.01	2.60				4	2	6	.21			.04
618.0	622.0	73828	4.0	.0	1D21	2.73	16.02	.02	.01	4.00				4	2	6	.22			.04
622.0	626.0	73829	4.0	.0	1D21	2.44	13.03	.03	.01	3.50				4	1	5	.18			.06
626.0	630.0	73830	4.0	.0	1D21	2.75	.08	.03	.18	1.50				4	1	5	.14			.06

include
what
(102)

*

DDH: 76916

---DEPTHS---		SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----												S.G. W.R.	
FROM	TO					CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %		As %
358.5	363.3	73850	4.8	.0 2H4	3.39	.33	5.02	5.96	62.10				7	23	31	.30			.17
365.0	367.2	73852	2.2	.0 2H4	2.94	.10	.82	1.36	16.40				7	23	31	.09			.17
367.2	371.0	73853	3.8	.0 2F4 ⁶⁰	5.13	.10	8.00	8.25	106.60				7	23	31	.10			.17
371.0	371.9	73854	.9	.0 2G4	5.46	.10	5.58	6.44	77.50				7	23	31	7.59			.17
371.9	376.5	73855	4.6	.0 2F4	5.75	.05	6.18	7.31	69.30				7	23	31	.06			.17
376.5	378.7	73856	2.2	.0 2H4	3.89	.32	4.77	5.48	59.00				6	29	35	.15			.21
378.7	380.4	73857	1.7	.0 2E4	6.17	.12	4.42	5.30	48.70				6	29	35	.04			.21
380.4	381.4	73858	1.0	.0 2H4 ⁶⁰	4.69	.25	7.38	9.30	87.10				6	29	35	.04			.21
381.4	389.5	73859	8.1	.0 2E4	4.31	.09	2.98	3.78	40.10				6	29	35	.02			.21
389.5	392.6	73860	3.1	.0 2BE4	4.81	.08	4.66	5.40	51.40				6	29	35	1.34			.21
392.6	396.0	73861	3.4	.0 2E4	4.49	.07	3.16	4.66	34.30				6	29	35	.14			.21
396.0	400.3	73862	4.3	.0 2H4 ⁷⁰	4.17	.48	6.75	8.98	72.70				17	20	37	.20			.42
400.3	401.6	73863	1.3	.0 2H4	3.86	.36	4.68	5.78	51.80				17	20	37	.10			.42
401.6	403.0	73864	1.4	.0 2F4	5.92	.29	5.70	6.53	70.30				17	20	37	.04			.42
403.0	408.0	73865	5.0	.0 2H4	3.94	.34	5.00	5.32	62.40				17	20	37	.06			.42
408.0	413.0	73866	5.0	.0 2F8	5.99	.19	4.20	3.60	56.60				17	20	37	.20			.42
413.0	418.0	73867	5.0	.0 2F8 ⁶⁰	4.52	.20	2.58	2.20	41.10				17	20	37	.04			.42
418.0	422.0	73868	4.0	.0 2F8	4.65	.18	3.95	3.65	59.00				3	20	23	.20			.14
422.0	423.9	73869	1.9	.0 1D4	3.02	.24	1.08	.98	25.70				3	20	23	1.17			.14
423.9	425.2	73870	1.3	.0 2G48	4.27	.22	5.14	5.12	88.80				3	20	23	1.96			.14
425.2	428.3	73871	3.1	.0 2F4	5.00	.09	5.85	5.70	76.80				3	20	23	.10			.14
428.3	433.3	73872	5.0	.0 2G4 ⁶⁰	4.69	.09	6.35	7.75	66.50				3	20	23	31.74			.14
433.3	435.0	73873	1.7	.0 2E4	4.61	.10	6.77	8.40	64.10				3	20	23	32.05			.14
435.0	436.6	73874	1.6	.0 2G0	4.07	.25	3.60	3.12	38.40				3	20	23	.98			.14
436.6	437.6	73875	1.0	.0 2E4	5.26	.09	3.09	3.92	30.20				5	35	41	9.51			.12
437.6	443.0	73876	5.4	.0 2E0	4.57	.22	1.32	1.32	16.40				5	35	41	.02			.12
443.0	447.6	73877	4.6	.0 2F0	4.55	.30	1.39	2.21	20.90				5	35	41	.04			.12
447.6	449.0	73878	1.4	.0 2E34 ⁵⁰	4.15	1.08	2.11	2.35	39.10				5	35	41	.04			.12
449.0	450.6	73879	1.6	.0 2E0	4.48	.79	1.06	1.26	21.60				5	35	41	.03			.12
450.6	451.0	73880	.4	.0 2F4	4.55	.12	8.28	9.40	89.80				5	35	41	.14			.12
451.0	456.0	73881	5.0	.0 2E4	4.59	.39	1.98	2.44	26.40				5	35	41	.03			.12
456.0	460.0	73882	4.0	.0 2L9	2.93	.09	1.10	3.80	15.80				12	4	17	.11			.03
460.0	463.0	73883	3.0	.0 2L9	2.63	.05	1.02	2.40	20.90				12	4	17	.11			.03
463.0	466.3	73884	3.3	.0 2A4	3.46	.04	.77	3.71	27.80				12	4	17	.13			.03
466.3	468.0	73885	1.7	.0 2E4	4.41	.03	4.00	6.65	38.40				12	4	17	.04			.03
468.0	471.0	73886	3.0	.0 2A4 ⁵⁰	2.87	.15	1.21	3.94	58.30				12	4	17	.30			.03
471.0	476.0	73887	5.0	.0 2H4	4.24	.44	4.21	6.45	42.90				12	4	17	.02			.03
476.0	479.0	73888	3.0	.0 2H4	4.27	.41	4.02	5.20	41.10				7	3	11	.07			.02
479.0	493.0	73889	14.0	.0 2D3	3.01	.19	.72	2.63	10.60				7	3	11	.13			.02
493.0	498.0	73890	5.0	.0 2A4	2.89	.06	.82	3.20	13.70				7	3	11	.10			.02
498.0	503.0	73891	5.0	.0 2A4	2.92	.03	1.35	3.15	31.20				2	1	4	.08			.03
503.0	508.0	73892	5.0	.0 2A4 ²¹	2.91	.06	1.88	3.15	31.50				2	1	4	.08			.03
508.0	513.0	73893	5.0	.0 2A4	2.97	.08	1.20	3.35	43.50				2	1	4	.07			.03
513.0	516.9	73894	3.9	.0 2A0	2.92	.07	1.17	1.85	47.30				2	1	4	.12			.03

DDH: 77-01

-----DEPTHS-----				-----ASSAYS-----																
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
568.8	573.8	73906	5.0	.0 2G4	4.61	.14	4.39	4.35	65.10		.41	3	27	31	8.90		.16			
573.8	578.8	73907	5.0	.0 2G4	4.65	50.13	6.28	6.48	83.80		.21	3	25	28	12.30		.12			
578.8	586.0	73908	7.2	.0 2E4	4.61	50.11	1.76	2.80	19.00		.07	1	37	38	.10					
586.0	597.0	73909	11.0	.0 2E14	4.02	50.02	2.02	3.49	21.00			2	32	34	.05					
597.0	601.0	73910	4.0	.0 2E1	3.55	.01	1.01	.49	11.40			1	29	30	.05					
601.0	607.0	73911	6.0	.0 2E1	3.07	.01	.01	.05	3.00			1	15	17	.05		.01			
607.0	612.0	73912	5.0	.0 2C3	3.70	40.23	.97	2.85	33.40			5	20	26	.05		.07			
612.0	617.0	73913	5.0	.0 2C3	3.78	.26	.01	.68	7.00			5	24	29	.10		.08			
617.0	622.0	73914	5.0	.0 2E1	3.92	.48	.96	1.63	13.30			6	27	33	.10		.22			
622.0	627.0	73915	5.0	.0 2E1	3.98	.28	.30	1.44	5.00			6	28	35	.05		.14			
627.0	632.0	73916	5.0	.0 2E1	3.98	40.22	1.43	2.32	8.70			6	26	33	.10		.16			
632.0	637.0	73917	5.0	.0 2E1	3.92	.50	.49	1.09	7.70			4	28	33	.05		.80			
637.0	642.0	73918	5.0	.0 2E1	3.82	.58	.27	.94	10.00			7	25	32	.05		.13			
642.0	647.0	73919	5.0	.0 2E84	4.08	.33	1.57	2.70	12.00		.07	6	27	34	.05		.18			
647.0	652.0	73920	5.0	.0 2E8	4.10	40.29	1.17	2.20	8.70		.01	8	28	36	.05		.23			
652.0	657.0	73921	5.0	.0 2C2	3.88	.22	.27	1.04	5.60		.27	2	26	29	.05		.05			
657.0	662.0	73922	5.0	.0 2E8	4.35	.34	.92	1.95	7.30		.01	8	30	38	.05		.14			
662.0	667.0	73923	5.0	.0 2E1	3.75	40.47	1.06	1.68	8.70		.07	5	23	29	.05		.13			
667.0	672.0	73924	5.0	.0 2E1	3.83	.22	.10	1.66	3.70			5	26	32	.05		.12			
672.0	675.0	73925	3.0	.0 2E1	4.01	.28	.04	1.34	4.40			5	30	36	.05		.12			
675.0	685.0	73926	10.0	.0 2F0	4.10	50.31	1.44	4.33	8.00			5	29	35	.05		.09			
685.0	690.0	73927	5.0	.0 1D4	3.83	12	1.42	5.38	13.30			6	22	28	.05		.09			

Waste

F8908

- Things to Check

Sect. 126

- 77-02 -

3490-3430

- Assays High !

- 74-08 -

3470

Lead + Silver Assay

122

DDH: 77-02

---DEPTHS---		SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														S.G. W.R.	
FROM	TO					CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %		
689.0	690.7	73984	1.7	.0	2F14	3.91	.22	6.33	16.70	52.30		.21	10	11	21	.05		.10			
690.7	695.5	73985	4.8	.0	2C0	3.34	.89	.35	1.08	40.00			9	10	20	.10		.11			
695.5	700.5	73986	5.0	.0	2C0	3.24	.52	.14	1.24	40.70			9	11	20	.10		.06			

DDH: 77-03

-----DEPTHS-----				-----ASSAYS-----																	
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %	S.G. W.R.	
520.5	525.0	73992	4.5	.0 2F4	4.12	10	4.30	9.80	31.10		.21	7	22	30	.05		.02				
525.0	530.0	73993	5.0	.0 2D4	3.88	50	3.81	6.30	35.60		.34	4	25	29	.05		.04				
530.0	535.0	73994	5.0	.0 2E1	4.12	20	.35	1.22	10.20			3	32	35	.05		.03				
535.0	540.0	73995	5.0	.0 2E1	4.03	33	.11	.51	10.20			5	30	35	.05		.05				
540.0	545.0	73996	5.0	.0 2E4	3.97	21	2.30	2.07	16.50		.14	1	29	31	.05		.01				
545.0	550.0	73997	5.0	.0 2E1	3.80	07	.13	1.50	7.30			2	27	30	.05		.02				
550.0	555.0	73998	5.0	.0 2E1	3.83	24	.33	.87	14.30			2	27	30	.05		.02				
555.0	560.0	73999	5.0	.0 2E1	3.94	28	.64	.70	9.70			2	30	33	.05		.03				
560.0	566.0	74000	6.0	.0 2E1	4.02	20	.91	1.28	21.50			3	30	33	.05		.04				
567.0	572.0	74002	5.0	.0 2E1	4.12	23	.77	1.06	20.40			3	32	35	.05		.03				
572.0	577.0	74003	5.0	.0 2E1	3.95	13	.81	2.46	9.70		.14	5	28	34	.05		.05				
577.0	582.0	74004	5.0	.0 2E1	4.08	12	1.04	2.18	16.70		.27	5	31	36	.05		.06				
582.0	586.0	74005	4.0	.0 2E8	4.39	20	.89	1.21	12.00		.99	7	32	40	.05		.10				
586.0	591.0	74006	5.0	.0 2E8	3.55	21	1.66	2.84	22.40		.41	4	20	25	.05		.09				
591.0	595.0	74007	4.0	.0 2E1	3.97	16	.52	2.18	6.00		.07	5	28	33	.05		.09				
595.0	598.0	74008	3.0	.0 2E1	4.22	28	.01	.91	5.30			3	33	37	.05		.09				
598.0	603.0	74009	5.0	.0 2E1	3.77	32	.06	.80	6.30			2	29	32	.05		.03				
603.0	609.0	74010	6.0	.0 2E1	3.78	35	.12	.60	62.90			2	25	28	.05		.02				
609.0	615.0	74011	6.0	.0 2E1	3.97	25	.23	.63	7.20			3	27	30	.05		.03				
615.0	621.0	74012	6.0	.0 2D4	3.51	05	3.56	8.98	17.00			4	15	19	.10		.03				
621.0	627.0	74013	6.0	.0 2C0	2.81	11	.96	2.14	10.40		.21	4	6	11	.10		.02				
627.0	635.0	74014	8.0	.0 2D4	3.39	09	4.38	13.20	40.90		.07	7	6	13	.10		.03				
635.0	638.0	74015	3.0	.0 0Q9	2.96	04	2.13	1.93	41.20		.89	2	3	6	.10		.04				

DDH: 77-07

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	---ASSAYS---							S.G. W.R.	
FROM	TO									Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe %	BAO %		Hg %
368.4	369.7	74031	1.3	.0	2E8	4.26	.12	4.95	3.24	100.00		.69	4	20	25	5.07		.20
369.7	375.0	74032	5.3	.0	2E8	4.95	.20	1.85	2.15	28.00		.82	12	27	40	.18		.62
375.0	380.0	74033	5.0	.0	2E0	4.13	40.17	1.22	1.06	17.20			5	28	33	.11		.16
380.0	385.0	74034	5.0	.0	2E1	4.48	.02	1.07	1.03	11.40			2	36	38	.07		.04
385.0	390.0	74035	5.0	.0	2C3	4.07	.01	.51	.42	8.60			1	30	32	.08		.03
390.0	395.0	74036	5.0	.0	2C3	3.44	.01	.46	.31	9.30			1	20	22	.08		.01
395.0	400.0	74037	5.0	.0	2E1	3.17	40.01	.47	.44	7.60			1	32	34	.08		.02
400.0	407.5	74038	7.5	.0	2C3	3.67	.04	.18	.23	6.30			1	27	28	.08		.01
407.5	412.0	74039	4.5	.0	0Q0	3.18	.21	.66	.12	48.00			1	12	14	.08		.01
412.0	415.6	74040	3.6	.0	2C3	3.97	50.03	1.22	1.57	11.70		.21	1	30	31	.11		.01
415.6	419.5	74041	3.9	.0	2F4	4.65	50.13	6.60	10.00	63.40		.21	2	31	34	.20		.06
419.5	425.0	74042	5.5	.0	2E4	4.08	.12	3.20	5.20	27.00		.14	2	27	29	.23		.03
425.0	430.0	74043	5.0	.0	2E1	3.89	.13	.88	1.04	11.40		.34	1	32	33	.20		.01
430.0	434.0	74044	4.0	.0	2C3	3.98	50.10	.96	1.30	9.70		.14	1	30	31	.21		.02
434.0	439.0	74045	5.0	.0	2E4	3.70	50.44	3.45	2.17	29.40		.21	1	27	28	.07		.01
439.0	443.4	74046	4.4	.0	2F4	4.31	.11	3.62	5.22	25.10		.07	1	31	32	.08		.01
443.4	447.0	74047	3.6	.0	2F4	4.78	.03	10.05	13.20	67.60		.62	1	28	30	.06		.03
447.0	452.0	74048	5.0	.0	2D4	3.53	.17	4.08	7.56	25.30		.14	3	17	20	.15		.23
452.0	457.2	74049	5.2	.0	2DE	3.75	32.14	2.20	4.20	14.60		.21	2	22	25	.11		.07
457.2	458.7	74050	1.5	.0	2F4	4.20	32.07	6.75	13.40	32.10		.41	4	23	27	.11		.21
458.7	462.7	74051	4.0	.0	2D8	4.05	.31	7.25	8.95	41.60		.21	6	19	25	.12		.50
462.7	466.0	74052	3.3	.0	2D8	4.10	.53	2.68	4.40	20.20			4	26	30	.15		.25
466.0	471.0	74053	5.0	.0	2E1	4.13	.40	.41	.74	14.50			2	32	35	.03		.05
471.0	477.3	74054	6.3	.0	2E1	3.98	.38	.50	.67	7.00			2	32	34	.04		.03
477.3	482.0	74055	4.7	.0	2E1	4.17	40.39	.99	1.60	7.80		.07	6	29	35	.08		.11
482.0	487.0	74056	5.0	.0	2E8	4.12	.29	1.50	1.88	12.10		.01	7	30	38	.10		.24
487.0	492.4	74057	5.4	.0	2E8	4.63	.29	.47	1.78	5.00			7	33	40	.11		.20
496.6	502.2	74059	5.6	.0	2D3	3.71	40.13	1.95	4.48	12.30		1.03	2	18	21	.11		.05
502.2	506.0	74060	3.8	.0	2C3	4.37	.23	.10	1.18	3.40			5	29	34	.07		.18
506.0	510.0	74061	4.0	.0	2C3	4.38	.31	.05	.89	3.90			2	29	32	.07		.10
510.0	515.0	74062	5.0	.0	2C3	4.33	.68	.60	1.20	6.80			3	29	32	.10		.09
515.0	518.0	74063	3.0	.0	2C3	4.28	40.14	.82	1.89	5.40		.01	4	28	32	.12		.12
518.0	522.2	74064	4.2	.0	2C3	4.42	.22	1.64	2.27	7.30		.01	4	28	32	.12		.12
522.2	527.2	74065	5.0	.0	2C3	4.44	.50	.06	1.04	5.10		.01	1	32	34	.04		.03
527.2	531.5	74066	4.3	.0	2C3	4.45	.20	1.45	2.90	5.80		.01	4	29	33	.06		.12
531.5	537.3	74067	5.8	.0	2D4	3.91	21.12	3.11	7.40	10.00		.01	3	21	25	.06		.04
537.3	542.0	74068	4.7	.0	2D0	3.22	.10	2.09	4.60	23.40		.14	4	4	9	.27		.06
542.0	551.0	74069	9.0	.0	2B0	2.72	.04	.96	2.18	13.10		.14	2	2	4	.27		.04
551.0	556.0	74070	5.0	.0	2B0	2.84	21.04	.94	2.01	11.00		.07	1	3	4	.64		.01
556.0	561.0	74071	5.0	.0	2B0	2.82	.04	1.12	2.23	12.30			1	2	3	.58		.01
561.0	566.0	74072	5.0	.0	2B5	2.50	.06	.89	2.28	13.00		.14	1	1	3	.49		.01
566.0	571.0	74073	5.0	.0	2B0	2.79	21.11	.68	2.08	12.40		.14	3	2	5	.37		.01
571.0	577.0	74074	6.0	.0	2B0	2.71	21.08	1.34	3.20	26.80		.27	2	1	3	.32		.02
577.0	582.2	74075	5.2	.0	2B0	2.86	.09	.67	2.20	9.80		.14	2	2	5	.61		.04
582.2	584.3	74076	2.1	.0	1D4	2.81	.05	.19	.23	2.80			3	3	6	.41		.13
584.3	587.0	74077	2.7	.0	1D4	2.82	.02	.04	.07	1.10			3	1	4	.32		.12
587.0	590.8	74078	3.8	.0	2A0	2.40	.01	.01	.05	1.20			3	1	4	.28		.17
590.8	594.8	74079	4.0	.0	2B0	2.72	.03	.02	.10	2.60			2	1	4	.27		.10
594.8	598.0	74080	3.2	.0	1D4	2.73	.05	.02	.11	3.90			2	1	3	.30		.07

Include waste
to E

DDH: 77-09

---DEPTHS---		SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														S.G. W.R.
FROM	TO					CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %	
516.8	520.8	74088	4.0	.0	2D0	3.34	33.18	5.83	2.60	78.60		.96	2	9	12	.30		.03		
520.8	525.0	74089	4.2	.0	2G4	4.32	.06	3.52	10.30	34.10		.01	2	18	21	8.48		.03		
525.0	531.0	74090	6.0	.0	2G4	4.78	60.03	2.12	4.46	19.80		.07	1	30	31	12.95		.02		
531.0	537.0	74091	6.0	.0	2G4	4.89	.09	3.95	6.62	37.90		.01	1	21	23	18.80		.06		
537.0	542.5	74093	5.5	.0	2D0	4.02	17	1.83	3.40	24.00		.01	1	24	25	3.94		.03		
<i>waste</i> 542.5	548.0	74094	5.5	.0	2D0	4.31	60.08	2.82	5.63	44.00		.14	3	24	27	6.00		.09		
577.0	578.0	74096	1.0	.0	2H14	5.11	.03	2.42	5.96	32.10		.07	2	37	40	.20		.04		
578.0	581.3	74097	3.3	.0	2H2	4.61	70.33	1.41	2.34	23.40		.01	29	15	45	.17		.10		
581.3	586.9	74098	5.6	.0	2C0	4.08	.05	1.40	.38	13.70		.07	2	31	33	.04		.04		
586.9	591.3	74099	4.4	.0	2E0	4.74	40.19	1.02	1.19	15.60		.07	3	37	41	.05		.12		
591.3	596.3	74100	5.0	.0	2E8	4.75	40.14	.76	1.36	9.50		.07	5	37	42	.02		.14		
596.3	599.3	74101	3.0	.0	2F0	4.82	.13	3.34	3.95	31.90		.07	4	36	40	.02		.09		
599.3	602.4	74102	3.1	.0	2F4	4.92	.06	6.00	12.30	45.30		.07	2	32	35	.02		.04		
602.4	607.4	74103	5.0	.0	2E34	5.00	50.08	3.46	6.75	22.90		.07	2	37	40	.02		.04		
607.4	611.6	74104	4.2	.0	2E3	4.83	50.26	2.78	4.14	21.60		.07	3	37	41	.02		.09		
611.6	616.6	74105	5.0	.0	2D3	4.30	.20	2.62	2.48	20.90		.07	3	31	35	.03		.09		
616.6	619.3	74106	2.7	.0	2E34	4.86	.09	2.46	3.90	19.60		.01	3	38	41	.03		.07		
619.3	623.3	74107	4.0	.0	2F4	4.91	.14	5.13	8.80	48.00		.06	3	32	35	.02		.13		
623.3	626.5	74108	3.2	.0	2F4	5.00	50.11	4.50	6.86	31.20		.06	3	34	38	.03		.11		
626.5	630.0	74109	3.5	.0	2E4	4.54	.24	4.95	8.38	47.90			5	29	34	.04		.13		
630.0	634.5	74110	4.5	.0	2E4	4.36	.29	2.20	2.54	25.00			4	32	37	.05		.16		
634.5	639.0	74111	4.5	.0	2E4	4.63	.33	2.79	3.38	26.90			5	30	36	.05		.26		
639.0	642.0	74112	3.0	.0	2E4	4.74	.25	3.26	5.68	21.00			7	30	38	.03		.33		
642.0	646.9	74113	4.9	.0	2E4	4.65	50.22	2.70	4.67	19.70			6	30	37	.04		.29		
646.9	650.0	74114	3.1	.0	2E4	4.14	.16	1.64	4.43	11.80		.03	6	27	33	.04		.20		
650.0	654.0	74115	4.0	.0	2E4	4.09	.34	1.38	4.20	12.70		.07	8	25	34	.03		.26		
654.0	657.5	74116	3.5	.0	2E34	4.29	.12	2.68	8.14	11.30		.07	7	26	33	.02		.24		
657.5	661.3	74117	3.8	.0	2E34	4.63	50.12	3.88	7.60	12.00		.01	5	30	35	.02		.20		
661.3	666.3	74118	5.0	.0	2E34	5.05	.15	3.24	5.17	12.90		.07	1	39	40	.01		.02		
666.3	671.3	74119	5.0	.0	2E34	4.85	.13	3.86	5.56	18.20		.07	1	38	40	.04		.03		
671.3	675.3	74120	4.0	.0	2E34	4.78	.18	2.91	4.41	13.10		.01	1	40	41	.03		.02		
675.3	678.9	74121	3.6	.0	2E34	4.42	.08	2.41	4.47	12.50		.07	1	36	38	.07		.02		
678.9	683.9	74122	5.0	.0	2D0	3.19	50.20	2.68	4.44	25.20		.14	7	9	16	.41		.06		
683.9	688.9	74123	5.0	.0	2D0	3.36	.40	2.69	6.73	29.60		.21	9	9	18	.41		.05		
688.9	692.5	74124	3.6	.0	2D0	3.36	.18	2.81	4.66	28.40		.14	7	16	24	.16		.06		

DDH: 77-10

---DEPTHS---		SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														S.G. W.R.
FROM	TO					CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %	
609.0	614.0	74181	5.0	.0 2D4	3.38	.05	3.72	9.85	27.20		.14	6	7	14	.30		.04			
614.0	619.0	74182	5.0	.0 2D4	3.51	.10	3.00	7.68	24.00		.07	11	8	20	.11		.02			
619.0	623.0	74183	4.0	.0 2C0 <i>21</i>	3.08	.06	1.36	2.27	16.20		.14	5	5	10	.29		.02			
623.0	625.6	74184	2.6	.0 2C0	2.92	.56	.60	1.94	37.90		.07	6	4	10	.18		.05			
625.6	628.0	74185	2.4	.0 1E0	2.77	.39	.22	.50	19.70			3	2	5	.25		.03			

DDH: 77-12

---DEPTHS---				-----ASSAYS-----																
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
228.2	231.2	74191	3.0	.0	2C3	3.55	.10	.30	.54	5.40				2	22	24	.23			.04
231.2	234.7	74192	3.5	.0	2AE4	4.08	.04	1.70	5.88	8.60				.21	2	28	30	.03		.03
234.7	237.3	74193	2.6	.0	2A4	3.54	.05	4.23	10.50	25.10				.41	2	14	16	.11		.02
237.3	241.0	74194	3.7	.0	2A4	3.55	.05	3.46	13.73	20.40				.34	3	13	16	.11		.03
241.0	244.0	74195	3.0	.0	2D0	3.53	.06	1.85	7.25	22.30				.48	3	16	19	.37		.05
244.0	247.3	74196	3.3	.0	2GH	4.49	.32	6.58	6.00	39.90				.41	14	17	32	7.82		.49
247.3	250.6	74197	3.3	.0	2G4	3.98	.17	10.35	5.52	51.00				.48	9	10	20	3.58		.36
250.6	253.6	74198	3.0	.0	2F4	4.55	.14	8.28	7.00	51.30				.34	9	21	31	5.49		.49
253.6	257.0	74199	3.4	.0	2B0	3.04	.14	.90	1.55	11.30				.07	5	3	8	7.36		.15
257.0	258.0	74200	1.0	.0	2G84	4.68	.08	7.04	6.00	64.20				.21	9	23	33	7.38		.58
258.0	259.7	74201	1.7	.0	2GH4	4.53	.28	5.31	5.27	83.50				.14	24	6	30	12.08		.59
259.7	263.5	74202	3.8	.0	2A4	3.10	.08	2.57	2.74	26.60				.07	6	4	11	3.20		.22
263.5	271.7	74203	8.2	.0	2B0	2.92	.03	.20	.54	1.50				.07	3	3	7	7.25		.07
271.7	275.7	74204	4.0	.0	2D0	3.56	.14	2.29	6.94	35.10				.07	9	14	24	1.56		.10
275.7	280.5	74205	4.8	.0	2D0	3.21	.16	1.86	4.75	26.10				.01	7	10	18	.59		.05
280.5	286.0	74206	5.5	.0	2F0	5.21	.10	3.05	5.15	22.00				.01	2	37	39	.05		.04
286.0	290.3	74207	4.3	.0	2H4	4.48	.58	4.82	7.46	48.70				.01	21	16	38	.04		.11
290.3	292.4	74208	2.1	.0	2F84	4.74	.13	5.73	9.85	55.10				.01	6	29	36	.03		.09
292.4	297.4	74209	5.0	.0	2D0	2.82	.10	.71	4.30	13.60				.07	6	4	10	.38		.06
297.4	302.4	74210	5.0	.0	2D0	2.76	.08	1.81	2.54	33.40				.01	4	3	8	.51		.04
302.4	307.0	74211	4.6	.0	2D0	2.82	.10	1.58	3.64	29.20				.07	7	2	9	.55		.03
307.0	310.0	74212	3.0	.0	2D0	3.08	.13	1.96	7.08	36.30				.07	13	1	15	.26		.03
310.0	315.0	74213	5.0	.0	2H4	4.18	.55	2.91	7.40	50.80				.07	46		46	.03		.03
315.0	319.7	74214	4.7	.0	2H4	4.10	.56	2.16	5.26	35.20				.07	49		49	.03		.03
319.7	321.0	74215	1.3	.0	2D0	3.17	.32	2.96	5.05	56.90				.07	19		19	.15		.04
321.0	324.0	74216	3.0	.0	2H0	4.14	.52	.32	.55	8.60				.27	47		47	.04		.02
324.0	329.0	74217	5.0	.0	2D0	3.20	.17	.84	5.54	13.80				.14	17	4	21	.17		.03
329.0	334.0	74218	5.0	.0	2D0	3.15	.10	1.57	4.97	27.20				.07	14	1	16	.45		.02
334.0	339.0	74219	5.0	.0	2D0	3.06	.13	3.66	5.64	60.30				.07	11	20	31	.56		.03
339.0	344.0	74220	5.0	.0	2A0	2.71	.08	.87	2.69	21.20				.07	5	3	9	.50		.02
344.0	349.0	74221	5.0	.0	2A4	2.78	.07	1.54	2.83	39.50				.21	7	2	10	.54		.01
349.0	354.0	74222	5.0	.0	2A0	2.89	.05	1.04	2.69	23.90				.14	3	4	7	.37		.01
354.0	359.5	74223	5.5	.0	2A4	2.66	.05	1.75	2.79	27.40				.21	2	1	3	.47		.01

285
0.13, 4.74, 7.01, 2789

20.2

14.0

DDH: 77-13

-----DEPTHS-----				-----ASSAYS-----																
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
376.0	380.0	74229	4.0	.0 2C0	3.35	.26	.02	.09	7.90					4 17 21	.12					.03
380.0	385.0	74230	5.0	.0 2C0	3.58	.14	.02	.05	10.90					2 19 21	.09					.04
385.0	389.0	74231	4.0	.0 2C0	3.59	.59	.04	.07	16.70					2 21 23	.05					.02
389.0	393.5	74232	4.5	.0 2C0	3.52	.44	.12	.18	23.70					2 22 25	.08					.04
393.5	395.5	74233	2.0	.0 2D0	4.55	.19	3.46	5.64	57.00					3 22 26	.33					.10
395.5	399.5	74234	4.0	.0 2G4	4.68	.16	5.93	5.45	78.80					6 21 28	10.69					.18
399.5	403.0	74235	3.5	.0 2G4	4.37	.27	5.44	5.17	75.30					10 19 29	10.51					.20
403.0	404.5	74236	1.5	.0 2H4	4.36	.59	3.36	3.11	62.20					18 17 36	.83					.18
404.5	405.8	74237	1.3	.0 2G4	4.63	.11	7.78	6.43	105.00					3 23 27	12.60					.16
405.8	409.7	74238	3.9	.0 2H4	4.14	.45	4.56	4.21	77.70					29 8 38	4.32					.19
409.7	411.0	74239	1.3	.0 2D4	3.31	.25	9.51	7.04	116.80					7 6 13	.52					.16
436.0	440.0	74241	4.0	.0 2D4	3.47	.13	5.97	7.65	83.60					11 9 21	.25					.17
440.0	444.0	74242	4.0	.0 2B4	3.17	.06	7.81	6.51	110.10					.07 6 6 13	.20					.15
444.0	447.0	74243	3.0	.0 2B4	3.02	.07	6.07	5.41	94.30					.01 5 4 10	.92					.14
447.0	450.0	74244	3.0	.0 2B0	2.79	.02	1.15	1.87	22.10					.01 3 2 6	2.07					.08
450.0	453.0	74245	3.0	.0 2D0	3.62	.20	3.84	6.08	66.80					.07 11 13 24	1.21					.12
453.0	457.0	74246	4.0	.0 2D4	3.90	.25	3.91	7.61	65.30					.07 13 18 32	.53					.11
457.0	459.0	74247	2.0	.0 2B0	3.14	.16	2.61	2.93	30.40					.07 7 9 16	1.31					.08
459.0	462.0	74248	3.0	.0 2B0	2.96	.06	1.93	2.54	21.40					.03 4 5 9	.88					.06
462.0	465.0	74249	3.0	.0 2B0	3.22	.07	2.85	5.01	39.50					.01 7 7 15	1.63					.09
465.0	470.0	74250	5.0	.0 2D0	3.87	.32	2.43	3.12	43.90					.01 15 19 35	.38					.11
470.0	474.0	74251	4.0	.0 2E14	4.60	.37	2.23	3.05	40.20					.01 15 25 40	.10					.12
474.0	477.0	74252	3.0	.0 2E14	4.18	.13	3.76	5.54	49.10					.01 9 26 36	.38					.10
477.0	482.6	74253	5.6	.0 2E4	4.75	.12	3.45	5.29	46.00					.07 5 32 38	.09					.06
482.6	485.0	74254	2.4	.0 2H4	4.32	.16	4.91	10.00	78.60					.01 19 14 34	.07					.09
485.0	487.0	74255	2.0	.0 2D0	3.09	.07	1.70	2.70	18.60					.01 9 7 16	.39					.09
487.0	491.0	74256	4.0	.0 2H4	4.23	.23	4.49	7.53	50.10					.01 13 23 37	.04					.09
491.0	496.4	74257	5.4	.0 2F4	4.63	.04	4.86	9.38	35.20					5 32 37	.03					.07
496.4	501.4	74258	5.0	.0 2F4	4.76	.05	6.08	10.26	42.20					.01 4 32 37	.02					.06
501.4	505.8	74259	4.4	.0 2F0	4.67	.08	3.14	6.49	23.90					.01 5 35 41	.03					.05
505.8	510.5	74260	4.7	.0 2H4	4.37	.20	4.00	8.78	30.80					.07 8 28 37	.03					.10
510.5	515.5	74261	5.0	.0 2D0	3.19	.09	2.62	6.94	32.40					.07 7 6 13	.24					.10
515.5	520.5	74262	5.0	.0 2D0	3.03	.08	1.70	4.17	27.70					.07 4 3 8	.36					.05
520.5	525.5	74263	5.0	.0 2D0	3.18	.08	1.24	4.73	25.10					.01 6 5 12	.38					.07
525.5	531.0	74264	5.5	.0 2D0	3.04	.07	.90	3.80	22.80					.07 5 5 11	.31					.05
531.0	536.7	74265	5.7	.0 2D0	3.14	.05	2.35	4.86	38.10					.07 5 3 8	.30					.04

Waste

17.5

21.0

41.5

all 400, 17.52, 39.62

DDH: 77-14

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													S.G. W.R.
FROM	TO						CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	
293.0	298.0	74268	5.0	.0	2C0	3.24	.20	.45	1.21	9.70				6	13	19	.37			.06
298.0	302.0	74269	4.0	.0	****	3.42	.05	.10	.05	4.40				2	2	4	.15			.02
302.0	307.0	74270	5.0	.0	2AC	3.10	.21	.05	.16	10.10				1	8	10	.21			.02
307.0	310.5	74271	3.5	.0	2AC	3.34	.21	.10	.49	13.40				1	12	13	.18			.01
310.5	314.0	74272	3.5	.0	2AC	3.80	.04	.72	2.78	8.50	.14			1	23	24	.11			.02
314.0	318.5	74273	4.5	.0	2F0	4.00	.24	4.71	9.32	75.60	.14			7	16	24	2.31			.16

DDH: 77-15

---DEPTHS---				-----ASSAYS-----																
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %	S.G. U.R.
400.0	405.0	74278	5.0	2C0	3.14	.29	.92	2.03	14.00		.34	6	10	16	.12		.04			
405.0	410.0	74279	5.0	2A4	3.51	13	1.81	5.79	17.50		.48	4	16	20	.12		.03			
410.0	416.0	74280	6.0	2A4	3.34	.11	1.83	6.93	17.90		.27	3	15	19	.50		.04			
416.0	420.6	74281	4.6	2D4	4.45	.25	5.74	6.59	57.20		.07	9	17	27	9.09		.31			
420.6	424.4	74282	3.8	2B0	2.90	.12	1.50	.42	9.00		.01	3	2	5	9.95		.05			
424.4	427.9	74283	3.5	2D0	3.22	.18	1.46	2.86	26.10		.01	5	7	13	9.06		.15			
427.9	431.2	74284	3.3	2D4	3.52	.19	4.59	5.73	34.90		.01	10	8	18	6.58		.24			
431.2	436.2	74285	5.0	2H14	4.29	.28	5.26	6.23	69.90		.07	18	16	35	4.81		.23			
436.2	441.0	74286	4.8	2H14	4.16	.24	4.29	6.50	60.80		.07	18	14	33	1.39		.13			
441.0	446.0	74287	5.0	2B0	3.01	.12	.90	2.43	14.10		.01	5	4	10	.76		.05			
446.0	450.0	74288	4.0	2B4	3.05	.12	1.44	3.95	23.30		.01	4	5	9	.45		.04			
450.0	454.0	74289	4.0	2B0	2.95	.08	1.05	2.52	21.10		.01	4	5	10	.72		.04			
454.0	458.0	74290	4.0	2B0	2.94	.09	.69	1.99	16.20		.07	4	2	7	.64		.05			
458.0	463.0	74291	5.0	2E4	4.63	.31	3.03	4.58	48.80		.07	12	28	41	.04		.10			
463.0	468.0	74292	5.0	2E4	4.63	.35	3.23	5.31	50.30		.01	13	27	40	.03		.09			
468.0	471.0	74293	3.0	2E4	4.21	.48	5.73	9.90	54.80		.14	16	18	34	.09		.12			

3.23 6.09

15.61
0.16 3.88 6.46 29.36

13.11

49.55
13.0

DDH: 77-16

---DEPTHS---				-----ASSAYS-----																
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
430.0	433.5	74299	3.5	.0 2A0	2.60	.01		.20	.10				3	1	4	.25				.08
433.5	437.0	74300	3.5	.0 2B2	2.68	.07	.11	.35	3.00				3	5	8	.87				.03
437.0	439.5	74301	2.5	.0 1D4	2.97	23.17	.13	.27	4.50				8	12	20	.54				.04
439.5	445.0	74302	5.5	.0 2A0	2.75	.13	.23	.43	5.30				6	7	14	.21				.04
445.0	450.0	74303	5.0	.0 2C0	2.88	.40	1.08	2.82	13.80				.07	6	8	14	.28			.07
450.0	455.0	74304	5.0	.0 2FG4	4.56	50.22	5.73	7.21	76.60				.07	8	24	32	6.76			.22
455.0	460.0	74305	5.0	.0 2FG4	4.59	.13	5.29	6.44	65.10			1.30	5	30	36	2.29				.17
460.0	463.5	74306	3.5	.0 2DG7	3.51	.26	3.71	4.97	53.60				.01	14	7	21	6.69			.12
463.5	467.0	74307	3.5	.0 2DG7	3.36	60.26	2.36	4.23	35.00				.27	6	9	15	10.99			.14
467.0	472.0	74308	5.0	.0 2G4	4.77	.20	5.87	6.22	82.50				.34	6	26	33	5.13			.21
472.0	477.0	74309	5.0	.0 2G0	4.51	.27	4.40	4.90	65.20				.48	6	23	29	15.41			.32
477.0	482.0	74310	5.0	.0 2G4	4.55	.19	5.76	6.59	82.40				.62	5	21	26	17.67			.29
482.0	487.0	74311	5.0	.0 2G4	4.67	60.22	5.44	6.98	80.70				.07	6	19	26	20.15			.28
487.0	492.0	74312	5.0	.0 2G4	4.56	.22	5.60	5.94	90.10				.34	7	22	29	13.42			.31
492.0	497.5	74313	5.5	.0 2G4	4.60	.26	5.89	6.44	85.10				.07	12	24	36	2.69			.19
497.5	501.5	74314	4.0	.0 2H4	4.31	70.22	6.81	8.35	99.70				.14	15	18	33	1.55			.14
501.5	506.5	74315	5.0	.0 2D0	3.01	.15	2.00	4.55	32.90				.01	8	5	14	.20			.05
506.5	510.0	74316	3.5	.0 2C0	2.84	21.14	.90	3.06	14.40				.01	6	4	10	.22			.03
510.0	514.5	74317	4.5	.0 2D0	3.03	2.00	.44	5.43	69.90			1.30	13	4	18	.23				.06
514.5	519.0	74318	4.5	.0 2A0	2.67	.27	.37	1.50	13.90				.07	5	1	6	.40			.06
519.0	522.0	74319	3.0	.0 2A0	2.61	.12	.05	.19	3.90				.01	5		6	.67			.08

.21 4.98 6.11 71.76

DDH: 77-17

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													S.G. W.R.
FROM	TO						CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	
459.0	464.0	74325	5.0	.0	2C0	2.95	.26	.10	.11	9.80		.33	8	11	20	.43		.06		
464.0	469.0	74326	5.0	.0	2D4	3.21	12	2.00	8.87	34.10		.14	6	9	15	.16		.09		
469.0	473.0	74327	4.0	.0	2DB4	3.28	13	2.05	4.81	36.00		.21	8	7	15	5.03		.18		
473.0	475.0	74328	2.0	.0	2G4	4.20	.07	6.43	6.47	109.30		.82	8	10	19	19.10		.32		
475.0	478.0	74329	3.0	.0	2H64	3.88	.04	4.81	5.18	66.20		.41	4	10	14	22.18		.17		
478.0	481.0	74330	3.0	.0	2H6	4.33	.24	5.19	4.00	77.50		.41	20	10	30	6.72		.44		
481.0	485.0	74331	4.0	.0	2G4	4.53	.12	6.57	4.97	102.70		.41	12	18	30	6.94		.38		
485.0	490.0	74332	5.0	.0	2G4	4.61	.08	7.24	6.13	97.30		.21	6	16	22	21.75		.33		
490.0	494.0	74333	4.0	.0	2G74	4.54	.20	7.67	5.44	108.00		.07	25	3	29	16.92		.42		
494.0	498.0	74334	4.0	.0	2G74	4.15	.32	5.41	5.23	78.80		.07	19	5	25	18.63		.36		
527.7	529.0	74336	1.3	.0	2D0	2.95	.05	1.30	1.96	25.40		.01	6	4	10	2.54		.13		
529.0	532.3	74337	3.3	.0	2B0	2.88	.05	1.11	1.70	19.60		.01	3	4	8	3.19		.07		
532.3	537.2	74338	4.9	.0	2D4	3.95	.22	4.64	7.33	77.00		.01	14	14	29	.11		.20		
537.2	540.2	74339	3.0	.0	2C0	2.81	.12	.70	.39	16.60		.01	2	5	7	.05		.02		
540.2	543.5	74340	3.3	.0	2D4	3.40	.11	9.26	17.00	17.00		.01	6	4	10	.11		.15		
543.5	548.5	74341	5.0	.0	2H8	4.30	.40	3.51	3.86	47.00		.01	32	12	44	.06		.11		
548.5	553.5	74342	5.0	.0	2H84	4.22	.45	5.45	6.27	80.70		.01	28	11	39	.19		.09		
553.5	555.1	74343	1.6	.0	2E14	4.70	.28	2.00	2.67	28.90		.01	11	31	43	.08		.09		
555.1	560.1	74344	5.0	.0	2F4	4.83	.09	5.88	9.57	49.00		.01	2	34	36	.04		.06		
560.1	564.1	74345	4.0	.0	2F0	5.04	.46	2.42	3.57	26.40		.01	1	41	43	.05		.02		
564.1	568.5	74346	4.4	.0	2F4	4.62	.07	3.75	7.11	27.30		.01	1	36	38	.02		.02		
568.5	573.5	74347	5.0	.0	2H84	4.53	.30	4.39	7.21	40.10		.01	23	18	41	.04		.08		
573.5	578.0	74348	4.5	.0	2H8	4.23	.46	2.50	3.75	29.30		.01	17	23	40	.03		.15		
578.0	581.0	74349	3.0	.0	2F0	4.55	.12	3.52	4.55	34.40		.01	6	32	38	.02		.09		
581.0	584.7	74350	3.7	.0	2F0	4.34	.22	3.14	4.88	28.50		.07	4	33	37	.03		.07		
584.7	587.0	74351	2.3	.0	2D0	3.01	.10	1.45	6.56	22.20		.01	6	7	14	.31		.04		
587.0	592.0	74352	5.0	.0	2C0	2.86	.08	1.68	2.18	19.00		.01	3	4	8	.29		.02		
592.0	597.0	74353	5.0	.0	2D0	2.89	.12	1.88	2.78	25.10		.01	4	4	8	.33		.03		
597.0	600.0	74354	3.0	.0	2D0	3.09	.13	2.23	1.95	26.10		.06	8	7	16	.38		.10		
600.0	604.0	74355	4.0	.0	2D0	3.33	.20	1.60	2.93	30.60		.07	8	11	20	.18		.09		
604.0	608.6	74356	4.6	.0	2DB	2.83	.04	2.29	4.69	41.40		.07	2	3	5	.19		.03		
608.6	611.0	74357	2.4	.0	2A0	2.71	.06	1.07	1.88	21.90		.07	3	3	6	.18		.04		
611.0	614.0	74358	3.0	.0	2A0	2.75	.08	1.59	2.38	23.40		.01	3	3	6	.23		.04		
615.7	617.6	74360	1.9	.0	2B4	3.07	.06	7.53	8.00	154.20		.07	5	2	7	.08		.10		
617.6	622.4	74361	4.8	.0	1D4	2.82	.06	.07	.07	6.00			4	3	7	.15		.04		

Waste

34.0' 5.17, 5.80, 7.73

46.8' 4.12, 6.50, 38.52

33

60

32

70

50

70

50

21

21

DDH: 77018

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													S.G. W.R.
FROM	TO						CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Pb %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	
243.0	247.0	74416	4.0	.0	****	3.51	.05	4.13	11.48	38.30			4	14	19	.14		.02		
247.0	252.0	74417	5.0	.0	****	4.87	.02	1.34	2.38	14.30			1	39	40	.01		.01		
252.0	257.0	74418	5.0	.0	****	3.28	.20	.88	3.76	14.20			9	12	21	.15		.04		
257.0	262.0	74419	5.0	.0	****	3.34	.13	.34	2.64	8.60			9	14	23	.14		.02		
262.0	267.0	74420	5.0	.0	****	3.39	.10	3.11	3.33	43.90			7	14	21	.15		.03		
267.0	272.0	74421	5.0	.0	****	3.33	.11	2.16	5.77	29.50			5	9	15	.22		.04		
272.0	277.0	74422	5.0	.0	****	3.48	.13	.92	6.69	17.10			6	13	20	.13		.06		
277.0	282.0	74423	5.0	.0	****	3.53	.09	1.24	4.81	18.60			4	19	23	.14		.03		
282.0	287.0	74424	5.0	.0	****	3.68	.24	1.28	2.98	17.10			8	18	26	.12		.04		
287.0	292.0	74425	5.0	.0	****	4.28	.43	4.77	3.74	33.80			11	24	35	.04		.07		
292.0	297.0	74426	5.0	.0	****	3.47	.14	1.90	3.33	24.50			5	19	25	.13		.02		

DDH: 77021

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													
FROM	TO						CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	PY %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %
9.5	13.0	74446	3.5	.0	****	3.26	.04	.92	2.70	9.50				6	14	21	.13		.15	
13.0	16.0	74447	3.0	.0	****	3.48	.02	.84	3.55	8.40				2	25	27	.14		.03	
16.0	21.0	74448	5.0	.0	****	3.77	.03	1.27	4.77	9.50				2	29	31	.11		.02	
21.0	26.0	74449	5.0	.0	ECO	3.25	.06	2.79	4.97	28.60				3	10	14	.20		.02	
26.0	31.0	74450	5.0	.0	****	3.20	.09	2.36	3.50	21.10				4	13	18	.20		.04	
31.0	36.0	74451	5.0	.0	****	3.21	.05	3.43	3.85	31.80				3	10	14	.20		.04	
36.0	41.0	74452	5.0	.0	****	2.98	.07	1.89	4.77	18.80				3	6	10	.27		.02	
41.0	43.5	74453	2.5	.0	****	3.49	.07	1.77	3.73	19.50				4	22	27	.22		.05	
43.5	47.5	74454	4.0	.0	****	4.31	.02	4.98	14.16	34.90				4	22	26	.02		.03	
47.5	50.5	74455	3.0	.0	****	3.05	.07	6.87	15.92	50.20				4	23	28	.02		.04	
50.5	53.5	74456	3.0	.0	****	3.23	.30	1.30	2.90	13.30				6	12	19	.21		.02	
53.5	57.0	74457	3.5	.0	****	3.41	.13	5.06	10.24	51.20				5	14	19	.06		.02	

DDH: 77023

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													S.G. U.R.
FROM	TO						CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	
12.0	16.0	74461	4.0	.0	****	3.23	.14	1.76	5.64	19.90			3	18	21	.11		.03		
16.0	21.0	74462	5.0	.0	****	3.40	.07	2.36	6.90	18.90			3	34	37	.12		.03		
21.0	26.0	74463	5.0	.0	****	3.28	.09	1.51	4.95	19.00			2	14	17	.14		.03		
26.0	31.0	74464	5.0	.0	****	3.16	.11	2.08	6.16	22.50			2	16	19	.09		.04		
31.0	36.0	74465	5.0	.0	****	3.42	.12	1.73	2.48	34.70			2	22	25	.11		.03		
36.0	41.0	74466	5.0	.0	****	3.49	.02	.68	2.97	11.60			1	27	29	.16		.01		
41.0	46.0	74467	5.0	.0	****	3.40	.05	1.36	4.77	17.90			3	17	20	.15		.02		
46.0	51.0	74468	5.0	.0	****	3.35	.04	3.36	7.86	44.60			1	17	18	.19		.01		
51.0	56.0	74469	5.0	.0	****	3.60	.02	3.94	9.20	39.60			1	17	19	.15		.01		
56.0	61.0	74470	5.0	.0	****	3.32	.03	4.01	8.20	41.20			2	14	17	.15		.02		
61.0	75.0	74471	14.0	.0	****	3.10	.02	1.29	5.41	18.10			2	11	14	.15		.01		
75.0	80.0	74472	5.0	.0	****	3.56	.02	.16	.29	6.10			2	23	25	.15		.01		
80.0	85.0	74473	5.0	.0	****	3.10	.02	2.80	4.44	36.40			2	11	14	.20		.01		
85.0	90.0	74474	5.0	.0	****	2.97	.02	2.34	5.89	34.10			3	6	10	.21		.02		
90.0	95.0	74475	5.0	.0	****	3.27	.06	3.84	8.43	40.20			3	9	12	.15		.03		
95.0	100.0	74476	5.0	.0	****	3.33	.03	.87	2.26	14.40			2	17	20	.18		.02		
100.0	105.0	74477	5.0	.0	****	4.78	.03	3.54	7.77	32.60			2	36	39	.03		.03		
105.0	111.0	74478	6.0	.0	****	3.12	.08	7.92	4.46	82.10			5	7	12	.34		.02		
111.0	117.0	74479	6.0	.0	****	3.37	.11	2.88	10.13	37.70			7	13	21	.07		.04		

DDH: 78005

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													S.G. W.R.
FROM	TO						CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	
18.1	20.6	74482	2.5	.0	****	2.97	.35	.76	1.05	10.30			7	8	16	.10		.09		
20.6	23.1	74483	2.5	.0	****	2.97	.06	1.80	4.49	10.30			1	5	6	.10		.02		
23.1	25.6	74484	2.5	.0	****	2.97	.04	1.53	2.70	10.30			1	3	4	.10		.02		
25.6	28.1	74485	2.5	.0	****	2.97	.04	1.39	2.71	10.30				4	4	.10		.02		
28.1	30.6	74486	2.5	.0	****	2.97	.03	1.20	1.98	10.30			1	5	7	.10		.03		
30.6	33.1	74487	2.5	.0	****	2.97	.05	1.93	3.32	10.30			6	3	9	.10		.09		
33.1	35.6	74488	2.5	.0	****	2.97	.20	3.11	3.98	10.30			10	11	21	.10		.16		
35.6	38.1	74489	2.5	.0	****	2.97	.29	3.06	.71	10.30			24	3	28	.10		.37		
38.1	40.6	74490	2.5	.0	****	4.42	.41	3.34	4.11	61.70			17	16	33	1.59		.35		
40.6	43.1	74491	2.5	.0	****	4.42	.36	3.98	5.32	61.70			19	17	36	1.59		.42		
43.1	45.6	74492	2.5	.0	****	4.42	.40	6.24	8.95	61.70			11	22	34	1.59		.30		
45.6	48.1	74493	2.5	.0	****	4.42	.29	5.84	8.97	61.70			14	18	33	1.59		.41		
48.1	50.6	74494	2.5	.0	****	4.42	.13	4.24	5.95	61.70			9	25	35	1.59		.39		
50.6	53.1	74495	2.5	.0	****	4.42	.34	4.55	6.52	61.70			14	17	32	1.59		.52		
53.1	55.6	74496	2.5	.0	****	4.42	.30	4.12	5.24	61.70			10	25	36	1.59		.40		
55.6	58.1	74497	2.5	.0	****	4.42	.25	5.86	7.60	61.70			10	26	36	1.59		.35		
58.1	60.6	74498	2.5	.0	****	4.65	.09	7.71	7.14	65.10			4	31	36	.93		.29		
60.6	63.1	74499	2.5	.0	****	4.65	.14	7.31	8.68	65.10			3	28	32	.93		.24		
63.1	65.6	74500	2.5	.0	****	4.65	.11	5.38	7.99	65.10			3	27	31	.93		.18		
65.6	68.1	74501	2.5	.0	****	4.65	.12	7.01	10.78	65.10			3	27	30	.93		.10		
68.1	70.6	74502	2.5	.0	****	4.65	.09	7.94	10.65	65.10			2	27	30	.93		.08		
70.6	73.1	74503	2.5	.0	****	4.65	.22	6.26	10.35	65.10			3	28	31	.93		.13		
73.1	75.6	74504	2.5	.0	****	4.65	.23	6.50	7.98	65.10			4	29	33	.93		.33		
75.6	78.1	74505	2.5	.0	****	4.65	.20	7.18	8.61	65.10			3	29	33	.93		.21		
78.1	80.6	74506	2.5	.0	****	4.61	.16	5.66	8.22	61.70			3	33	36	.68		.29		
80.6	83.1	74507	2.5	.0	****	4.61	.18	6.31	8.09	61.70			3	27	30	.68		.16		
83.1	85.6	74508	2.5	.0	****	4.61	.19	5.42	7.91	61.70			5	27	32	.68		.24		
85.6	88.1	74509	2.5	.0	****	4.61	.49	5.89	7.21	61.70			4	29	34	.68		.16		
88.1	90.6	74510	2.5	.0	****	4.61	.45	23.50	8.52	61.70			23	14	38	.68		.34		
90.6	93.1	74511	2.5	.0	****	4.61	.25	9.80	10.12	61.70			5	27	32	.68		.36		
93.1	95.6	74512	2.5	.0	****	4.61	.32	6.06	6.44	61.70			6	30	37	.68		.41		
95.6	98.1	74513	2.5	.0	****	4.61	.14	5.45	5.88	61.70			5	32	37	.68		.29		
98.1	100.6	74514	2.5	.0	****	4.05	.15	4.20	4.76	72.00			5	31	36	1.02		.28		
100.6	103.1	74515	2.5	.0	****	4.05	.21	7.33	7.66	72.00			4	28	33	1.02		.21		
103.1	105.6	74516	2.5	.0	****	4.05	.31	4.94	6.28	72.00			5	30	36	1.02		.29		
105.6	108.1	74517	2.5	.0	****	4.05	.28	4.96	7.50	72.00			6	25	31	1.02		.11		
108.1	110.6	74518	2.5	.0	****	4.05	.27	4.06	10.21	72.00			18	7	25	1.02		.11		
110.6	113.1	74519	2.5	.0	****	4.05	.12	1.88	6.98	72.00			5	5	10	1.02		.07		
113.1	115.6	74520	2.5	.0	****	4.05	.05	3.08	4.13	72.00			3	3	6	1.02		.05		
115.6	118.1	74521	2.5	.0	****	4.05	.07	9.00	5.35	72.00			2	4	7	1.02		.04		
118.1	120.6	74522	2.5	.0	****	3.91	.05	1.63	1.80	44.60			2	2	5	.03		.05		
120.6	123.1	74523	2.5	.0	****	3.91	.03	6.62	3.41	44.60			2	1	3	.03		.05		
123.1	125.6	74524	2.5	.0	****	3.91	.01	2.39	2.01	44.60			1		1	.03		.03		
125.6	128.1	74525	2.5	.0	****	3.91	.03	2.72	4.33	44.60			2	1	3	.03		.04		
128.1	130.6	74526	2.5	.0	****	3.91	.34	2.63	5.06	44.60			8	20	29	.03		.09		
130.6	133.1	74527	2.5	.0	****	3.91	.26	5.73	8.49	44.60			33	8	42	.03		.13		
133.1	135.6	74528	2.5	.0	****	3.91	.55	2.76	2.64	44.60			50	2	52	.03		.05		
135.6	138.1	74529	2.5	.0	****	3.91	.52	3.26	3.10	44.60			50	1	52	.03		.04		
138.1	140.6	74530	2.5	.0	****	3.33	.48	3.66	4.12	17.10			39	3	42	.06		.04		
140.6	143.1	74531	2.5	.0	****	3.33	.55	4.23	8.29	17.10			44	2	46	.06		.06		
143.1	145.6	74532	2.5	.0	****	3.33	.29	3.33	13.01	17.10			13	3	17	.06		.21		

DDH: 78005

---DEPTHS---			SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													S.G. W.R.
FROM	TO	CU %						Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %	
145.6	148.1	74533	2.5	.0	****	3.33	.06	1.63	7.08	17.10				3	3	6	.06		.12		
148.1	150.6	74534	2.5	.0	****	3.33	.06	.16	.70	17.10				2	3	5	.06		.04		
150.6	153.1	74535	2.5	.0	****	3.33	.05	.03	.06	17.10				2	3	6	.06		.04		
153.1	155.6	74536	2.5	.0	****	3.33	.02	.07	.08	17.10				2	3	5	.06		.04		
155.6	158.1	74537	2.5	.0	****	3.33	.02	.03	.07	17.10				2	2	4	.06		.04		
158.1	160.6	74538	2.5	.0	****	2.79	.08	2.84	4.38	30.90				4	2	7	.10		.09		
160.6	163.1	74539	2.5	.0	****	2.79	.07	2.80	4.64	30.90				3	4	8	.10		.08		
163.1	165.6	74540	2.5	.0	****	2.79	.09	1.68	3.93	30.90				2	3	6	.10		.02		
165.6	168.1	74541	2.5	.0	****	2.79	.09	1.26	2.09	30.90				1	2	3	.10		.01		
168.1	170.6	74542	2.5	.0	****	2.79	.05	1.72	3.88	30.90				1	2	4	.10		.03		
170.6	173.1	74543	2.5	.0	****	2.79	.08	.62	1.06	30.90				2	1	4	.10		.06		

DDH: 78006

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													S.G. W.R.
FROM	TO						CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	
5.0	8.0	74546	3.0	.0	****	5.18	.37	5.20	5.04	65.10			3	24	28	24.00			.27	
8.0	10.5	74547	2.5	.0	****	5.18	.17	6.93	7.42	65.10			3	16	20	24.00			.37	
10.5	13.0	74548	2.5	.0	****	5.18	.10	5.66	7.13	65.10			2	12	15	24.00			.25	
13.0	16.0	74549	3.0	.0	****	5.18	.29	1.67	1.41	65.10			1	37	38	24.00			.06	
16.0	19.1	74550	3.1	.0	****	5.18	.23	4.04	3.62	65.10			2	33	36	24.00			.13	
19.1	23.2	74551	4.1	.0	****	4.39	.17	1.01	.49	17.10				30	31	.03			.02	
23.2	27.6	74552	4.4	.0	****	4.39	.60	2.22	3.42	17.10			2	37	40	.03			.09	
27.6	29.1	74553	1.5	.0	****	4.39	.37	5.26	7.53	17.10			20	18	39	.03			.09	
29.1	31.6	74554	2.5	.0	****	4.39	.43	3.48	5.32	17.10			5	33	38	.03			.06	
31.6	34.1	74555	2.5	.0	****	4.39	.24	3.06	4.70	17.10			3	34	37	.03			.11	
34.1	36.6	74556	2.5	.0	****	4.39	.32	2.63	4.77	17.10			2	36	38	.03			.07	
36.6	39.1	74557	2.5	.0	****	4.39	.62	4.49	7.09	17.10			20	19	39	.03			.05	
39.1	41.6	74558	2.5	.0	****	3.03	.20	1.45	3.18	27.40			3	3	7	.10			.04	
41.6	44.1	74559	2.5	.0	****	3.03	.14	1.43	3.05	27.40			2	2	5	.10			.03	
44.1	46.6	74560	2.5	.0	****	3.03	.26	2.75	3.80	27.40			5	6	11	.10			.03	
46.6	49.1	74561	2.5	.0	****	3.03	.61	2.17	4.85	27.40			17	7	24	.10			.04	
49.1	51.6	74562	2.5	.0	****	3.03	.25	.77	2.24	27.40			3	5	9	.10			.03	
51.6	54.1	74563	2.5	.0	****	3.03	.23	2.68	6.00	27.40			4	3	8	.10			.09	
54.1	56.6	74564	2.5	.0	****	3.03	.13	2.17	2.62	27.40			1	1	2	.10			.04	
56.6	59.1	74565	2.5	.0	****	3.03	.21	.82	.55	27.40			3	3	7	.10			.03	

DDH: 78022

---DEPTHS---		SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														S.G. W.R.
FROM	TO					CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %	
8.0	23.0	74568	15.0	.0	****	4.69	.32	1.67	3.04	8.10				3	38	41	.20			.08
23.0	43.0	74569	20.0	.0	****	4.35	.23	4.93	9.26	12.80				4	26	30	.20			.12
43.0	63.0	74570	20.0	.0	****	4.87	.14	4.57	8.18	8.40				1	21	23	.17			.02
63.0	83.0	74571	20.0	.0	****	4.64	.10	1.56	3.44	8.10				2	37	39	.36			.01
83.0	103.0	74572	20.0	.0	****	3.78	.17	4.06	9.86	25.50				1	36	38	.21			.03

DDH: 78023

-----DEPTHS-----					-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
3.0	23.0	74575	20.0	.0 ****	4.51	.31	3.39	2.80	26.70				3	29	32	3.07				.12
23.0	43.0	74576	20.0	.0 ****	4.48	.30	2.01	3.60	25.60				4	25	30	.19				.14
43.0	63.0	74577	20.0	.0 ****	4.85	.35	3.05	5.19	13.10				1	33	35	.19				.03
63.0	83.0	74578	20.0	.0 ****	4.64	.33	2.10	4.26	9.60				2	30	33	.20				.07
83.0	103.0	74579	20.0	.0 ****	4.72	.25	2.92	4.74	17.40				5	4	10	.19				.04
103.0	123.0	74580	20.0	.0 ****	4.15	.19	3.78	5.84	28.00				4	8	13	.26				.07

DDH: 78024

---DEPTHS---		SAMPLE NO.	INT. 20.0	REC. .0	ROCK UNIT	S.G. PULP	-----ASSAYS-----													S.G. W.R.		
FROM	TO						CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %		Ba %	
13.0	33.0	74583	20.0	.0	****	4.14	.07	3.85	7.49	12.10			1	28	30	.21		.03				
33.0	53.0	74584	20.0	.0	****	4.20	.07	3.96	7.34	17.10			3	20	23	.19		.05				
53.0	73.0	74585	20.0	.0	****	3.29	.07	.90	1.90	24.30			2	29	31	.31		.01				
73.0	93.0	74586	20.0	.0	****	3.40	.11	.92	1.35	9.30			2	36	39	.27		.03				
93.0	113.0	74587	20.0	.0	****	4.36	.08	2.46	3.82	38.20			1	36	37	.18		.01				
113.0	133.0	74588	20.0	.0	****	4.44	.07	1.38	2.31	12.40			1	5	6	.19		.02				
133.0	153.0	74589	20.0	.0	****	2.72	.11	1.19	1.64	15.60			1	10	12	.37		.03				
153.0	163.0	74590	10.0	.0	****	2.93	.15	1.42	2.52	13.70			3	36	39	.34		.02				

DDH: 78025

					-----ASSAYS-----															
---DEPTHS---		SAMPLE INT.	REC.	ROCK	S.G.	CU	Pb	Zn	Ag(AA)	Ag(FA)	Au(FA)	Po	Py	TOT	BAO	Hg	Mn	As	Ba	S.G.
FROM	TO	NO.		UNIT	PULP	%	%	%	g/mT	g/mT	g/mT	%	%	Fe	%	%	%	%	%	U.R.
11.0	26.0	74593	15.0	.0	****	4.73	.50	3.23	4.82	21.10				1	20	22	.20			.05
26.0	46.0	74594	20.0	.0	****	3.61	.30	3.08	5.81	29.90				3	35	39	.27			.02
46.0	66.0	74595	20.0	.0	****	3.34	.31	11.00	2.16	120.00				6	2	8	.24			.06
66.0	86.0	74596	20.0	.0	****	2.78	.33	.29	.54	19.30				5	15	20	.30			.06

DDH: 78026

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													S.G. W.R.
FROM	TO						CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	
10.0	21.0	74599	11.0	.0	****	4.63	.48	1.79	3.86	8.40			6	33	40	.19		.18		
21.0	41.0	74600	20.0	.0	****	4.40	.36	.58	1.93	21.80			7	29	37	.19		.19		
41.0	61.0	74601	20.0	.0	****	4.60	.52	1.18	2.92	19.60			4	33	38	.19		.10		
61.0	81.0	74602	20.0	.0	****	4.36	.31	4.04	6.56	10.30			2	36	38	.20		.05		
81.0	101.0	74603	20.0	.0	****	4.20	.06	4.10	8.94	4.70			1	38	39	.21		.02		
101.0	121.0	74604	20.0	.0	****	3.62	.16	1.70	3.97	16.20			3	3	6	.23		.02		

DDH: 78027

-----DEPTHS-----				-----ASSAYS-----																	
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %	S.G. W.R.	
6.0	21.0	74607	15.0	.0 ****	3.01	.15	2.03	3.56	23.30			3	3	7	.27		.04				
21.0	31.0	74608	10.0	.0 ****	2.61	.20	1.95	3.55	17.70			5	16	21	.26		.01				

DDH: 79-03

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													S.G. W.R.
FROM	TO						CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	
139.2	140.0	74616	.8	.0	2D09	3.40	.30	2.55	1.69	41.80			.44	10	7	17	.80		.30	
140.0	145.0	74617	5.0	.0	2E46	4.57	.24	6.89	6.43	120.00			.31	16	10	27	1.70		.43	
145.0	150.0	74618	5.0	.0	2E46	4.55	60 .16	6.76	5.96	111.50			.45	5	18	23	2.00		.38	
150.0	155.0	74619	5.0	.0	2E46	4.68	.11	7.49	7.67	100.50			.72	4	16	20	2.60		.28	
155.0	160.0	74620	5.0	.0	2E46	4.72	.17	7.46	6.41	112.20			.84	8	15	24	2.30		.39	
160.0	165.0	74621	5.0	.0	2E46	4.74	.15	6.39	5.56	90.50			.61	7	18	26	2.00		.46	
165.0	170.0	74622	5.0	.0	2E46	4.58	60 .13	7.15	5.98	104.10			.64	6	14	20	2.50		.44	
170.0	175.0	74623	5.0	.0	2E46	4.60	.09	3.74	3.90	57.60			.53	3	25	29	1.80		.18	
175.0	180.0	74624	5.0	.0	2G40	4.67	.08	4.70	5.83	34.30			.78	2	22	25	2.10		.12	
180.0	185.0	74625	5.0	.0	2E4	4.78	.02	3.51	5.72	46.70			.23	2	32	34	1.20		.02	
185.0	188.5	74626	3.5	.0	2D4	4.01	33 .09	3.47	10.30	52.50			.36	3	18	22	1.10		.04	
227.5	230.0	74628	2.5	.0	2D0	4.08	.15	3.36	3.63	29.20			.14	2	28	31			.02	
230.0	235.0	74629	5.0	.0	2D09	4.09	.13	.69	.46	8.60			.09	1	33	34			.01	
235.0	240.0	74630	5.0	.0	2F00	4.43	40 .24	2.15	3.46	20.60			.08	1	35	37			.01	
240.0	245.0	74631	5.0	.0	2C3	4.54	.27	1.19	1.49	11.00			.06	2	38	41			.10	
245.0	250.0	74632	5.0	.0	2F00	4.46	.18	1.42	1.93	4.50			.05	8	34	42			.36	
250.0	255.0	74633	5.0	.0	2F4	4.61	.15	6.50	9.71	44.90			.04	7	28	35			.30	
255.0	260.0	74634	5.0	.0	2E4	4.70	50 .16	2.66	4.10	13.00			.03	6	35	42			.19	
260.0	265.0	74635	5.0	.0	2D40	4.36	.17	5.73	8.92	20.60			.18	5	27	32			.10	
265.0	270.0	74636	5.0	.0	2D4	3.80	.11	3.87	3.49	78.60			.93	1	24	26			.03	
270.0	275.0	74637	5.0	.0	2D4	3.78	50 .11	4.03	8.02	18.20			.37	3	20	23			.03	
275.0	280.0	74638	5.0	.0	2F40	4.16	.12	4.90	8.41	23.70			.38	5	24	30			.18	
280.0	285.0	74639	5.0	.0	2F40	4.08	.16	4.96	9.70	12.70			.12	7	21	28			.28	
285.0	290.0	74640	5.0	.0	2F40	4.03	.19	.36	3.38	2.10			.07	10	22	32			.29	
290.0	295.0	74641	5.0	.0	2C39	3.75	40 .24	.14	1.20	3.10			.09	7	21	29			.18	
295.0	300.0	74642	5.0	.0	2C39	4.01	.36	.07	1.61	2.10			.07	7	25	33			.18	
300.0	305.0	74643	5.0	.0	2C39	3.77	.62	.06	.97	4.10			.07	7	21	28			.17	
305.0	310.0	74644	5.0	.0	2E09	3.98	.41	.27	1.53	2.10			.05	9	25	35			.25	
310.0	315.0	74645	5.0	.0	2E09	4.11	40 .25	.13	1.36	2.10			.05	9	26	36			.26	
315.0	320.0	74646	5.0	.0	2C39	4.01	.43	.27	1.68	3.80			.05	6	28	34			.17	
320.0	325.0	74647	5.0	.0	2C39	4.30	.55	.06	.87	3.40			.04	4	34	38			.15	
325.0	330.0	74648	5.0	.0	2E1	4.39	.52	.02	.81	2.40			.05	5	35	40			.15	
330.0	335.0	74649	5.0	.0	2E1	4.27	40 .18	.02	1.14	1.00			.05	4	34	39			.13	
335.0	340.0	74650	5.0	.0	2E1	4.43	.11	.35	2.41	1.70			.05	4	35	39			.11	
340.0	345.0	74651	5.0	.0	2F4	4.48	.08	4.69	9.12	9.30			.05	3	29	33			.08	
345.0	350.0	74652	5.0	.0	2E4	4.31	50 .03	7.46	12.10	22.30			.05	2	23	26			.02	
350.0	355.0	74653	5.0	.0	2E4	4.33	.03	5.13	11.00	18.20			.05	3	25	28			.02	
355.0	360.0	74654	5.0	.0	2D0	3.57	.04	1.45	4.64	7.60			.09	3	17	21			.06	
360.0	365.0	74655	5.0	.0	2D05	3.74	50 .06	.95	3.10	6.90			.07	2	22	25			.02	
365.0	370.0	74656	5.0	.0	2E00	4.70	.02	2.37	4.96	13.40			.07	1	37	38			.01	
370.0	375.0	74657	5.0	.0	2E0	4.89	.01	.94	.66	6.90			.05	4	40	45			.01	
375.0	380.0	74658	5.0	.0	2E0	4.86	40 .01	.08	.17	.70			.05	3	42	45			.01	
380.0	385.0	74659	5.0	.0	2E0	4.86	.02	.96	1.82	6.90			.05	3	40	44			.01	
385.0	390.0	74660	5.0	.0	2C3	4.51	.05	.78	2.02	17.20			.06	3	36	40			.02	
390.0	395.0	74661	5.0	.0	2C3	3.38	.11	.48	1.65	8.90			.06	3	17	20			.01	
395.0	400.0	74662	5.0	.0	2D0	3.35	21 .09	2.70	4.22	50.10			.08	3	12	15			.03	
400.0	401.0	74663	1.0	.0	2D0	3.12	.09	2.95	3.26	78.20			.05	4	5	10			.04	

subste interval

DDH: 80-01

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----												
FROM	TO						CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %
532.5	535.0	74722	2.5	.0	2A4	2.96	.16	1.41	3.06	28.00			3	5	8	.18		.02	
535.0	537.5	74723	2.5	.0	2A0	2.77	.03	.84	2.53	11.80			1	1	3	.21		.02	
537.5	540.0	74724	2.5	.0	2A0	2.76	.02	1.06	2.70	16.80			1		2	.17		.02	
540.0	542.5	74725	2.5	.0	2A0	2.87	.14	1.58	3.52	27.60			3	2	6	.21		.03	
542.5	545.0	74726	2.5	.0	2A0	3.04	.19	.96	1.92	36.00			6	6	13	.14		.04	
545.0	547.5	74727	2.5	.0	2A0	2.77	.08	.96	2.30	15.90			2	2	5	.16		.03	
547.5	550.0	74728	2.5	.0	2A0	2.74	.07	.69	2.52	9.00			3		3	.30		.05	
550.0	552.5	74729	2.5	.0	2A0	2.84	.06	1.04	2.53	14.90			4	1	6	.12		.09	
552.5	555.0	74730	2.5	.0	2A4	2.99	.11	.68	5.99	61.90			3	2	6	.39		.04	
555.0	557.5	74731	2.5	.0	2A4	2.76	.04	.95	2.67	9.90			2	1	4	.20		.05	
557.5	560.0	74732	2.5	.0	2A0	2.79	.05	.63	1.23	13.40			2	1	3	.27		.02	
560.0	562.5	74733	2.5	.0	2A4	2.85	.15	.91	3.18	28.60			3	2	5	.15		.04	
562.5	565.0	74734	2.5	.0	2A4	2.88	.17	.98	3.63	29.20			3	2	5	.20		.04	
565.0	567.5	74735	2.5	.0	2A0	2.96	.29	.32	2.65	18.00			4	6	11	.15		.03	
567.5	570.0	74736	2.5	.0	2A0	3.10	.17	.61	2.42	22.10			5	8	13	.13		.03	
570.0	572.5	74737	2.5	.0	2A4	2.97	.14	.68	3.37	21.80			4	4	8	.17		.03	
572.5	575.0	74738	2.5	.0	2A4	2.87	.14	1.30	2.65	24.90			2	2	5	.12		.03	
575.0	577.5	74739	2.5	.0	2A0	2.84	.14	.97	2.22	25.20			2	2	5	.15		.02	
577.5	580.0	74740	2.5	.0	2A0	2.78	.09	.49	.75	11.20			2	2	4	.33		.02	
580.0	584.0	74741	4.0	.0	2A0	2.76	.10	.90	1.70	14.60			1	1	3	.18		.02	
423.0	425.0	80025	2.0	.0	2L14		.01	.03	.01	2.80			1	2	3	3.56		.03	
425.0	427.5	80026	2.5	.0	2L14		.05	.98	1.18	20.53			2	2	5	3.55		.11	
427.5	430.0	80027	2.5	.0	2L14		.07	1.97	2.48	42.30			3	4	7	3.91		.18	
430.0	431.5	80028	1.5	.0	2L14		.11	1.40	1.76	32.97			4	6	10	3.82		.16	
431.5	435.0	80029	3.5	.0	2L14		.04	.56	.86	19.28			4	2	6	4.28		.10	
435.0	437.5	80030	2.5	.0	2L14		.07	1.00	1.78	31.17			4	4	9	6.79		.12	
437.5	440.0	80031	2.5	.0	2A0		.13	.70	1.45	29.86			3	4	8	9.45		.09	
440.0	442.0	80032	2.0	.0	2L14		.15	3.37	3.02	87.81			6	5	12	5.53		.21	
442.0	444.0	80033	2.0	.0	2L14		.18	1.61	1.99	50.39			5	4	10	3.80		.17	
444.0	446.0	80034	2.0	.0	2D4		.18	10.90	6.87	261.26			10	8	18	4.57		.45	
446.0	448.0	80035	2.0	.0	2L14		.08	4.46	1.18	87.71			2	2	4	6.39		.10	

*Waste
Intermittent
same as above*

DDH: 80-02

---DEPTHS---				-----ASSAYS-----																
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
641.0	643.5	74799	2.5	.0 2A0	2.85	.08	1.47	2.19	19.00		.55	2	4	7	.16					.01
643.5	646.0	74800	2.5	.0 2A0	2.91	.11	.65	.46	14.30		.41	2	5	7	.14					.02
646.0	648.5	74801	2.5	.0 2A0	2.98	.13	1.33	2.25	22.10		.55	3	4	8	.13					.04
648.5	651.0	74802	2.5	.0 2A0	2.77	.08	.36	.59	9.90			3	2	6	.13					.02
651.0	653.5	74803	2.5	.0 2A0	2.89	.08	.11	.49	3.39			2	3	6	.14					.02
653.5	656.0	74804	2.5	.0 2A0	2.93	.10	.28	.65	5.90			3	6	9	.16					.02
656.0	658.5	74805	2.5	.0 2A0	2.89	.14	.28	.36	6.79			3	3	6	.14					.02
658.5	661.0	74806	2.5	.0 2A0	2.75	.11	.20	.33	6.50			1	1	3	.34					.02
661.0	663.5	74807	2.5	.0 2A0	2.74	.05	.58	1.47	13.99			1	1	3	.20					.02
663.5	666.0	74808	2.5	.0 2A4	3.58	.07	1.23	3.83	18.00		.14	1	1	3	.14					.04
666.0	668.5	74809	2.5	.0 2A4	2.19	.05	1.62	4.69	22.69		.14	1		2	.11					.02
668.5	671.0	74810	2.5	.0 2A4	2.68	.08	1.68	3.06	34.20		.21	1		2	.14					.01
671.0	673.5	74811	2.5	.0 2A0	2.83	.17	.84	.72	21.80			3	4	7	.14					.02
673.5	676.0	74812	2.5	.0 2A0	2.87	.14	.28	.65	19.30			3	3	6	.14					.02
676.0	678.5	74813	2.5	.0 2A0	2.83	.22	.39	.40	33.00			3	4	8	.17					.02

DDH: 80-03

-----DEPTHS-----							-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %	S.G. W.R.	
577.5	582.5	74870	5.0	.0	2E4	4.30	.18	2.35	3.42	10.60		.07	5	28	33	.05						.23
582.5	585.0	74871	2.5	.0	2E4	4.07	.12	1.86	2.84	21.80		.01	4	28	32	.04						.17
585.0	587.5	74872	2.5	.0	2F0	4.91	.03	2.73	6.32	25.80		.07		38	38	.04						.04
587.5	590.0	74873	2.5	.0	2F4	4.60	.04	4.39	7.93	28.00		.01	1	34	36	.05						.04
590.0	595.0	74874	5.0	.0	2F4	4.56	.07	3.44	7.49	21.20		.07	1	33	35	.05						.06
595.0	600.0	74875	5.0	.0	2F4	5.04	.04	2.88	6.63	17.40		.01	1	38	39	.04						.02
600.0	602.5	74876	2.5	.0	2C0	3.07	.11	.58	1.95	6.20			5	8	14	.33						.06
602.5	605.0	74877	2.5	.0	2D0	3.23	.16	1.64	4.88	21.20		.14	6	9	16	.15						.10

DDH: 80-04

Waste to
610.5

---DEPTHS---		SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	---ASSAYS---					Hg %	Mn %	As %	Ba %	S.G. W.R.
FROM	TO											Po %	Py %	TOT Fe %	BAO %						
582.5	585.0	74883	2.5	.0	2F6	4.53	4.43	7.47	69.00		.07	2	25	27	8.72		.05				
610.5	613.0	74886	2.5	.0	2E84	4.43	.13	3.64	3.45	47.00		.21	6	28	35	.18		.24			
613.0	615.5	74887	2.5	.0	2E4	4.57	.08	2.57	2.69	21.80		.07	2	36	38	.10		.06			
615.5	618.0	74888	2.5	.0	2E0	4.18	.03	.87	.55	7.20		.07		36	37	.11		.01			
618.0	620.5	74889	2.5	.0	2E4	4.34	.07	1.59	2.51	11.20		.07	1	35	36	.10		.01			
620.5	624.0	74890	3.5	.0	2A0	3.98	.01	.44	.80	3.70			1	31	33	.05		.01			
624.0	628.0	74891	4.0	.0	2EC	3.79	.02	1.30	2.38	6.80		.07	1	27	28	.10		.03			
628.0	630.5	74892	2.5	.0	2ED	3.43	.18	1.39	3.50	11.20			4	15	20	.18		.14			
630.5	633.0	74893	2.5	.0	2ED	4.04	.18	3.13	6.83	10.00			5	23	28	.12		.10			
633.0	635.5	74894	2.5	.0	2ED	3.91	.24	3.87	9.44	12.10			6	17	24	.08		.08			
635.5	638.0	74895	2.5	.0	2A1	2.96	.11	.87	3.05	10.90		.14	3	4	8	.28		.03			
638.0	641.5	74896	3.5	.0	2A1	2.90	.06	1.10	2.06	12.40		.14	2	3	5	.31		.03			
641.5	645.0	74897	3.5	.0	2A1	2.77	.05	.82	1.84	10.30		.07	2	1	3	.34		.03			
645.0	648.5	74898	3.5	.0	2A1	2.74	.05	.74	1.81	8.70		.14	1	1	2	.33		.03			
648.5	651.0	74899	2.5	.0	2C5	2.95	.21	2.56	1.08	37.90		.41	3	4	8	.45		.03			
651.0	653.5	74900	2.5	.0	2C5	2.89	.13	1.00	1.16	9.60			6	4	11	.24		.08			
653.5	656.0	74901	2.5	.0	2C5	2.92	.17	.74	.89	8.10			5	3	8	.30		.07			
656.0	658.5	74902	2.5	.0	2C5	3.02	.20	.54	1.43	6.80			6	5	12	.24		.06			
658.5	661.0	74903	2.5	.0	2D4	3.48	.27	4.51	9.86	43.50		.07	7	9	17	.12		.04			
661.0	663.5	74904	2.5	.0	2A1	2.88	.13	1.20	.84	24.30			3	5	8	.24					
663.5	666.0	74905	2.5	.0	2A1	2.77	.09	.33	.64	10.30			2	2	4	.27		.02			
666.0	668.5	74906	2.5	.0	2A1	2.83	.14	.29	.89	15.60			2	3	5	.24		.04			
668.5	671.0	74907	2.5	.0	2A1	2.81	.10	.51	.79	16.80			1	3	5	.19		.04			

DDH: 80-05

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	---ASSAYS---					S.G. W.R.		
FROM	TO												Po %	Py %	TOT Fe	BAO %	Hg %		Mn %	As %
446.0	449.0	74911	3.0	.0	2C0	2.99	.18	.37	3.42	12.10			6	12	18	.03				.09
449.0	452.0	74912	3.0	.0	2D0	3.31	.15	2.93	6.89	44.50			7	11	19	.01				.17
452.0	455.0	74913	3.0	.0	2F49	4.25	.26	5.67	8.32	81.80			9	24	34	.03				.24
455.0	457.5	74914	2.5	.0	2F4	4.60	.10	8.62	10.27	103.30			3	23	27	6.60				.10
457.5	460.0	74915	2.5	.0	2G4	4.59	.16	7.48	8.41	98.00			2	18	21	19.46				.09
460.0	462.5	74916	2.5	.0	2G4	5.47	.16	6.67	7.99	90.50			2	18	21	19.44				.12
462.5	465.0	74917	2.5	.0	2G4	4.64	.14	6.60	7.93	78.10			2	16	18	23.35				.11
465.0	467.5	74918	2.5	.0	2F4	4.68	.17	9.81	10.50	112.00			2	28	30	.06				.04
467.5	470.0	74919	2.5	.0	2G4	4.38	.15	7.88	8.75	90.50			2	17	19	20.17				.09
470.0	472.5	74920	2.5	.0	2F4	4.78	.17	6.52	7.99	74.30			2	29	32	4.58				.09
472.5	475.0	74921	2.5	.0	2F4	4.14	.16	7.25	9.80	82.70			3	24	28	.59				.07
475.0	477.5	74922	2.5	.0	2F49	5.11	.21	7.89	10.20	89.30			4	26	30	3.40				.10
477.5	480.0	74923	2.5	.0	2F4	4.76	.19	6.25	7.59	69.40			4	30	34	2.44				.19
480.0	484.0	74924	4.0	.0	2F4	4.90	.08	6.45	9.43	56.90			1	31	33	.01				.03
484.0	487.5	74925	3.5	.0	2F4	5.64	.13	9.22	8.92	81.80			5	27	32	.03				.13
487.5	490.5	74926	3.0	.0	2F46	4.92	.19	7.45	7.26	79.30			4	24	29	8.69				.11
490.5	493.5	74927	3.0	.0	2F49	5.78	.21	7.61	9.03	79.30			7	26	33	.41				.14
493.5	496.5	74928	3.0	.0	2H49	4.30	.51	5.05	7.75	92.70			28	11	40	.10				.07
496.5	499.0	74929	2.5	.0	2A4	3.28	.16	2.32	4.52	35.80			6	8	14	.43				.04
499.0	501.5	74930	2.5	.0	2A4	3.09	.09	1.41	3.43	25.50			4	3	8	.31				.03
501.5	504.0	74931	2.5	.0	2A0	3.15	.08	.79	2.11	17.10			3	4	7	.29				.02
504.0	506.5	74932	2.5	.0	2A0	2.97	.07	.60	1.39	15.20			3	4	7	.24				.02
506.5	509.0	74933	2.5	.0	2A0	2.88	.04	.83	1.67	21.50			2	2	4	.24				.03
509.0	511.5	74934	2.5	.0	2A0	2.95	.06	1.02	2.14	23.30			3	3	6	.22				.03
511.5	514.0	74935	2.5	.0	2A4	3.36	.07	3.06	5.40	57.90			4	3	7	.29				.05
514.0	516.5	74936	2.5	.0	2A4	3.21	.07	1.95	3.25	42.90			5	4	9	.38				.07
516.5	519.0	74937	2.5	.0	2A0	3.04	.13	1.00	1.41	27.40			4	5	9	.41				.02
519.0	521.5	74938	2.5	.0	2A4	3.10	.11	1.71	2.98	40.10			5	6	11	.22				.03
521.5	524.0	74939	2.5	.0	2A0	3.11	.10	1.44	2.14	31.70			3	2	6	.43				.01
524.0	526.5	74940	2.5	.0	2D5	3.25	.13	1.54	3.19	50.10			5	10	16	.29				.01
526.5	529.0	74941	2.5	.0	2D5	3.09	.16	1.70	4.47	47.60			4	5	10	.36				.02
529.0	531.5	74942	2.5	.0	2D59	3.11	.20	1.75	5.09	67.20			5	6	11	.27				.03
531.5	534.0	74943	2.5	.0	2D5	3.09	.19	2.23	4.43	87.10			5	7	12	.29				.04
534.0	536.5	74944	2.5	.0	2D5	3.19	.14	2.51	4.82	84.30			5	5	11	.20				.08
536.5	539.0	74945	2.5	.0	2C5	2.93	.09	1.03	1.70	24.30			3	4	7	.27				.03

118 6.75 8.43 79.13

DDH: 80-06

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													S.G. W.R.
FROM	TO						CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	
611.0	613.0	75003	2.0	.0	2E19	3.96	.26	.40	1.36	15.60				2	26	29	.03			.09
613.0	616.0	75004	3.0	.0	2E89	4.30	.33	.33	1.97	7.80				9	27	36				.44
616.0	619.0	75005	3.0	.0	2E48	4.30	.28	1.45	3.04	10.30				8	28	36	.01			.33
619.0	621.5	75006	2.5	.0	2F49	4.46	.39	3.33	7.82	19.00				6	26	32	.02			.24
621.5	624.0	75007	2.5	.0	2F49	4.35	.26	4.58	7.67	20.80				5	37	42	.03			.18
624.0	626.5	75008	2.5	.0	2F4	4.70	.14	3.60	8.75	22.70				3	29	33	.01			.10
626.5	629.0	75009	2.5	.0	2F9	4.43	.37	1.96	4.39	15.60				4	28	33	.01			.16
629.0	631.5	75010	2.5	.0	2F4	4.80	.05	5.16	8.69	48.50				2	31	33	.01			.05
631.5	634.0	75011	2.5	.0	2F4	4.90	.06	5.72	10.71	28.90				3	27	31				.06
634.0	636.5	75012	2.5	.0	2F49	4.12	.26	5.73	12.20	34.20				5	20	25	.01			.09
636.5	639.0	75013	2.5	.0	2F4	4.97	.05	4.87	10.07	28.60				2	31	33	.01			.03
639.0	641.5	75014	2.5	.0	2F4	4.73	.06	7.30	12.40	42.30				2	28	31	.01			.03
641.5	644.0	75015	2.5	.0	2F4	4.76	.05	6.86	10.50	39.50				1	31	33				.02
644.0	646.5	75016	2.5	.0	2F4	5.00	.03	6.83	10.50	39.50				1	31	33	.01			.02
646.5	649.0	75017	2.5	.0	2F4	4.80	.01	8.37	14.90	45.70				1	27	29	.01			.02
649.0	651.5	75018	2.5	.0	2D5	3.48	.12	1.26	3.52	27.40				1	19	21	.03			.02
651.5	654.0	75019	2.5	.0	2D5	3.49	.06	.87	3.52	16.50				1	16	17	.06			.01
654.0	656.5	75020	2.5	.0	2D45	3.32	.17	4.86	7.07	44.80				2	12	15	.06			.02
656.5	659.0	75021	2.5	.0	2C5	3.49	.04	.21	2.29	13.40				1	17	19	.06			.02
659.0	661.5	75022	2.5	.0	2C5	3.55	.03	.40	2.98	20.50				1	20	22	.06			.01
661.5	664.0	75023	2.5	.0	2D5	3.54	.02	1.42	3.95	16.50				1	18	19	.04			.01
664.0	666.5	75024	2.5	.0	2D4	3.28	.04	7.18	2.82	55.10				1	20	21	.08			.01
666.5	669.0	75025	2.5	.0	2D4	3.27	.08	6.32	14.05	32.00				2	8	10	.06			.01
669.0	671.5	75026	2.5	.0	2D4	3.49	.03	8.20	16.00	36.70				2	8	10	.07			.01
671.5	674.0	75027	2.5	.0	2D4	3.61	.02	9.60	16.37	36.70				2	9	12	.06			.01
674.0	676.5	75028	2.5	.0	2D4	3.69	.03	10.15	18.26	39.80				2	9	11	.06			.01
676.5	679.0	75029	2.5	.0	2D4	3.43	.03	5.15	16.21	25.20				2	9	11	.06			.01
679.0	681.5	75030	2.5	.0	2D4	3.49	.02	10.20	17.22	41.40				2	8	11	.07			.01
681.5	684.0	75031	2.5	.0	2D4	3.31	.03	6.04	15.18	24.60				2	6	8	.11			.01
684.0	686.5	75032	2.5	.0	2D4	3.68	.04	10.63	18.79	33.30				3	7	10	.07			.02
686.5	689.0	75033	2.5	.0	2D4	3.81	.02	7.33	15.98	23.90				2	12	15	.04			.01
689.0	691.5	75034	2.5	.0	2D4	3.53	.04	6.40	14.95	20.50				2	11	13	.06			.01
691.5	694.0	75035	2.5	.0	2D4	3.80	.02	7.42	15.92	28.30				2	13	15	.03			.01
694.0	696.5	75036	2.5	.0	2D4	3.50	.02	5.74	14.05	21.20				2	11	13	.08			.01
696.5	699.0	75037	2.5	.0	2D4	3.41	.17	6.46	13.96	33.00				4	8	12	.10			.03
699.0	701.5	75038	2.5	.0	2D4	5.87	.10	5.14	13.03	32.70				3	13	16	.08			.05
701.5	704.0	75039	2.5	.0	2D0	3.20	.07	.78	7.72	44.80				2	11	14	.10			.05
704.0	706.5	75040	2.5	.0	2D4	3.32	.12	4.37	6.86	36.40				6	15	21	.07			.07
706.5	709.0	75041	2.5	.0	2D4	3.15	.16	3.95	8.65	29.90				5	6	11	.09			.09
709.0	711.5	75042	2.5	.0	2A0	2.96	.19	.70	2.54	14.30				6	4	10	.18			.05
711.5	714.6	75043	3.1	.0	2B00	2.95	.14	.35	.15	13.10				1	3	5	.01			.01
714.6	717.8	75044	3.2	.0	2B4*	3.05	.11	7.63	3.04	114.10				2	2	5	.03			.11
717.8	721.0	75045	3.2	.0	2B4*	3.13	.16	3.87	12.10	24.90				5	3	8	.07			.13
721.0	723.5	75046	2.5	.0	2D47	3.50	.40	4.66	13.73	28.00				13	2	15	.08			.08
723.5	726.0	75047	2.5	.0	2D47	3.36	.34	2.29	10.72	19.90				13	4	17	.06			.09
726.0	728.0	75048	2.0	.0	2D79	3.40	.27	1.89	4.64	26.70				19	2	22	.07			.11

DDH: 80-07

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	---ASSAYS---				S.G. W.R.		
FROM	TO												Po %	Py %	TOT Fe	BAO %		Hg %	Mn %
614.5	617.0	75107	2.5	.0	2E4	4.91	.06	2.93	4.70	14.60			1	41	42	.03		.02	
617.0	619.5	75108	2.5	.0	2E4	4.87	.12	2.87	4.80	22.40			1	40	42	.04		.02	
619.5	623.0	75109	3.5	.0	2H90	4.31	.47	3.22	6.61	51.90			41	4	45	.07		.07	
623.0	626.0	75110	3.0	.0	2H9	4.24	.58	2.99	6.31	49.80			41	7	49	.05		.07	
626.0	628.5	75111	2.5	.0	2D49	3.29	.25	3.60	8.05	43.50			8	5	14	.32		.07	
628.5	631.0	75112	2.5	.0	2D49	3.37	.18	9.70	3.55	150.80			6	7	14	.33		.05	
631.0	633.5	75113	2.5	.0	2F9	4.04	.26	4.92	4.45	354.60			6	22	28	.14		.07	
633.5	636.0	75114	2.5	.0	2D0	3.21	.15	1.68	3.67	88.00			3	9	13	.14		.05	
636.0	638.0	75115	2.0	.0	2D0	2.95	.12	1.30	4.33	37.00			4	3	7	.25		.04	
638.0	640.0	75116	2.0	.0	2H0	4.45	.63	3.29	6.15	19.60			35	6	42	.39		.04	
640.0	642.5	75117	2.5	.0	2E40	4.55	.14	4.85	8.68	24.60			4	28	32	.06		.03	
642.5	645.0	75118	2.5	.0	2E40	5.06	.03	4.14	5.61	11.80			2	30	32	.03		.03	
645.0	647.5	75119	2.5	.0	2E40	4.95	.04	4.81	5.22	49.10			3	33	36	.04		.05	
647.5	650.0	75120	2.5	.0	2E40	4.87	.02	6.17	7.29	19.90			3	34	37	.05		.05	
650.0	652.5	75121	2.5	.0	2E40	5.02	.03	3.56	5.07	11.20			1	33	35	.05		.03	
652.5	655.0	75122	2.5	.0	2E40	4.89	.01	7.42	10.18	131.90			2	32	34	.04		.03	
655.0	657.5	75123	2.5	.0	2E40	5.32	.01	6.11	7.01	18.40			1	35	37	.04		.02	
657.5	660.0	75124	2.5	.0	2E40	5.12	.02	5.28	11.30	19.00			2	32	34	.04		.03	
660.0	662.0	75125	2.0	.0	2E41	4.04	.03	3.35	7.44	12.40			1	26	27	.07		.04	
662.0	664.5	75126	2.5	.0	2F41	4.16	.02	4.22	9.12	14.30			1	26	28	.08		.04	
664.5	667.0	75127	2.5	.0	2F41	4.34	.92	6.08	14.80	23.60			2	25	28	.06		.03	
667.0	670.0	75128	3.0	.0	2E41	3.38	.03	1.12	4.68	10.60			1	16	18	.09		.03	
670.0	672.5	75129	2.5	.0	2E41	3.54	.04	2.76	8.43	17.70			2	17	20	.05		.05	
672.5	675.0	75130	2.5	.0	2A41	3.37	.12	4.57	11.30	60.70			3	8	11	.08		.04	
675.0	678.0	75131	3.0	.0	2A41	3.02	.21	3.21	6.49	69.00			3	2	5	.13		.04	
678.0	680.5	75132	2.5	.0	2A41	3.56	.36	1.03	6.62	19.60			8	13	21	.09		.07	
680.5	683.0	75133	2.5	.0	2D39	3.28	.36	1.43	6.69	22.10			6	9	16	.20		.04	
683.0	685.5	75134	2.5	.0	2D39	3.33	.37	.95	6.00	23.00			7	13	20	.18		.04	
685.5	688.0	75135	2.5	.0	2D39	3.43	.50	1.40	3.64	21.50			8	15	24	.15		.08	
688.0	690.5	75136	2.5	.0	2D39	3.22	.29	1.86	7.38	24.30			5	12	17	.16		.04	
690.5	693.0	75137	2.5	.0	2D0	2.98	.18	2.18	5.49	28.60			4	3	7	.30		.01	
693.0	695.5	75138	2.5	.0	2D0	3.00	.16	1.89	7.02	29.90			3	4	8	.36		.06	
695.5	699.0	75139	3.5	.0	2D43	3.35	.28	7.91	5.31	133.10			10	4	15	.17		.02	

DDH: 80-08

DEPTHS FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	ASSAYS					S.G. W.R.	
												Po %	Py %	TOT Fe %	BAO %	Hg %		Mn %
409.0	412.0	75143	3.0	0	2L14	3.32 <i>ubsk</i>	.05	4.32	7.78	128.80		4	3	8	15.65		.15	
412.0	414.5	75144	2.5	0	2D4	3.98	.13	5.55	7.81	111.00		11	14	25	6.89		.26	
414.5	417.0	75145	2.5	0	2G1	3.07	.10	1.85	2.21	31.70		7	6	14	13.98		.13	
417.0	419.5	75146	2.5	0	2G4	4.07 <i>33</i>	.17	4.29	5.84	89.90		14	8	22	16.15		.20	
419.5	422.0	75147	2.5	0	2D46	3.61	.19	5.30	7.06	128.10		12	12	24	3.05		.33	
422.0	425.0	75148	3.0	0	2L14	3.22	.19	1.85	2.09	38.60		11	9	20	4.47		.19	
425.0	428.0	75149	3.0	0	2L14	2.82	.06	.27	.34	6.80		15	5	20	.92		.16	
428.0	430.5	75150	2.5	0	2D6L	3.77	.16	5.71	3.12	128.10		4	12	16	12.98		.14	
430.5	433.0	75151	2.5	0	2C6L	3.03 <i>33</i>	.22	1.64	.64	37.00		4	5	10	11.48		.13	
433.0	435.5	75152	2.5	0	2C6	2.97	.10	.42	.33	12.40		3	3	7	8.89		.12	
435.5	437.5	75153	2.0	0	2C69	3.24	.30	2.06	1.70	38.30		6	12	18	5.47		.32	
437.5	440.0	75154	2.5	0	2E41	4.57	.29	4.32	3.91	68.70		6	22	28	5.55		.23	
440.0	442.5	75155	2.5	0	2E09	4.68	.24	4.17	4.11	65.60		5	26	32	7.47		.25	
442.5	445.0	75156	2.5	0	2E49	5.56	.20	1.91	2.20	29.20		2	37	39	.22		.09	
445.0	447.5	75157	2.5	0	2E09	4.67 <i>60</i>	.31	1.95	1.26	25.20		2	33	36	.57		.09	
447.5	450.0	75158	2.5	0	2E0	4.52	.16	1.34	1.41	18.70		1	36	37	.34		.02	
450.0	452.5	75159	2.5	0	2E0	4.54	.14	.74	.69	15.20		1	37	39	.10		.04	
452.5	455.0	75160	2.5	0	2E4	4.15	.06	1.85	2.89	17.70		1	30	32	.45		.03	
455.0	457.5	75161	2.5	0	2E4	4.71	.16	3.85	5.92	38.30		2	34	36	.10		.07	
457.5	460.0	75162	2.5	0	2E0	5.89	.12	1.30	.63	19.00			39	40	.45			
460.0	462.5	75163	2.5	0	2E0	4.03	.12	1.51	.75	21.20			39	40	.57		.01	
462.5	465.0	75164	2.5	0	2E0	4.47 <i>40</i>	.09	2.24	1.44	32.00		1	35	36	.10		.01	
465.0	467.5	75165	2.5	0	2E0	4.22	.13	1.08	.69	17.70		1	34	35	.34		.03	
467.5	470.0	75166	2.5	0	2E0	4.77	.12	1.82	1.83	27.70		1	39	40	.34		.02	
470.0	472.5	75167	2.5	0	2E0	4.32	.14	1.64	1.27	26.40		2	32	35	.45		.03	
472.5	475.0	75168	2.5	0	2E09	3.93	.29	1.84	1.13	33.60		2	32	34	.57		.08	
475.0	478.0	75169	3.0	0	2E49	4.75 <i>40</i>	.36	2.50	1.69	48.50		3	35	38	.22		.16	
478.0	481.0	75170	3.0	0	2E09	3.29	.34	1.68	.66	36.70		3	34	37	.22		.10	
481.0	483.5	75171	2.5	0	2E6	4.98	.10	.99	1.22	30.80		1	33	35	3.13		.05	
483.5	486.0	75172	2.5	0	2G4	4.42	.06	2.94	7.60	42.90		1	9	11	20.91		.05	
486.0	488.5	75173	2.5	0	2E06	4.51	.36	1.52	2.46	26.10		6	30	37	4.80		.29	
488.5	491.0	75174	2.5	0	2E89	5.64	.46	1.37	1.68	29.20		10	27	38	.22		.30	
491.0	493.5	75175	2.5	0	2E48	4.50 <i>60</i>	.40	4.13	4.85	56.90		8	28	37	.10		.34	
493.5	496.0	75176	2.5	0	2E48	4.64	.19	9.15	3.30	131.90		3	29	32	.10		.12	
496.0	498.5	75177	2.5	0	2E48	4.45	.33	2.42	4.11	74.30		8	28	37	.34		.39	
498.5	501.5	75178	3.0	0	2E48	4.35	.32	1.61	3.34	23.00		10	26	37	.22		.46	
501.5	504.5	75179	3.0	0	2E48	4.61	.40	1.55	2.91	20.50		9	29	39	.69		.45	
504.5	507.0	75180	2.5	0	2E48	4.71 <i>60</i>	.25	1.98	3.26	21.20		5	32	37	.22		.38	
507.0	509.5	75181	2.5	0	2E19	4.80	.44	.82	.43	13.40		1	40	41	.22		.15	
509.5	512.0	75182	2.5	0	2E1	4.68	.12	1.43	1.79	15.60		2	34	37	.10		.02	
512.0	514.0	75183	2.0	0	2E41	4.44	.27	2.84	3.88	23.90		6	28	35	.34		.07	
514.0	516.0	75184	2.0	0	2E48	4.68	.26	1.65	2.51	15.90		4	34	38	.22		.24	
516.0	518.0	75185	2.0	0	2E48	4.81	.17	2.47	2.98	22.40		4	33	38	.10		.15	
518.0	520.0	75186	2.0	0	2E89	4.73	.31	.87	2.10	15.60		8	31	39	.22		.30	
520.0	522.5	75187	2.5	0	2E48	4.37	.52	2.75	2.80	40.70		8	26	34	.34		.35	
522.5	525.0	75188	2.5	0	2E89	4.61 <i>50</i>	.23	1.12	1.56	15.90		9	31	41	.22		.45	
525.0	527.5	75189	2.5	0	2E1	4.92	.19	.24	.32	19.60		5	35	41	.10		.18	
527.5	530.0	75190	2.5	0	2E19	4.89	.24	.24	.21	12.40		3	36	40	.57		.11	
530.0	532.5	75191	2.5	0	2E41	4.52	.15	3.20	4.68	22.70		6	31	37	.57		.17	
532.5	535.0	75192	2.5	0	2E1	4.32	.15	1.60	1.64	14.60		7	29	37	.34		.22	
535.0	537.5	75193	2.5	0	2E1	4.22	.15	1.32	1.74	14.00		4	28	33	.34		.11	

DDH: 80-08

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													
FROM	TO						CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %
537.5	540.0	75194	2.5	.0	2F0	4.50	.16	2.70	5.49	15.60					3	25	29	.22		.09
540.0	542.5	75195	2.5	.0	2F4	4.36	.17	2.94	7.24	14.30					5	25	31	.22		.16
542.5	545.0	75196	2.5	.0	2F41	4.34	.27	7.39	12.40	18.70					4	22	26	.22		.16
545.0	547.5	75197	2.5	.0	2E19	4.19	.37	1.97	4.43	10.60					6	26	32	.34		.19
547.5	550.0	75198	2.5	.0	2E1	4.28	.20	.99	2.90	10.90					3	30	33	.22		.09
550.0	552.5	75199	2.5	.0	2E41	4.40	.16	1.83	3.87	15.60					3	28	32	.10		.09
552.5	555.0	75200	2.5	.0	2E41	4.50	.17	2.63	4.17	14.60					2	31	34	.57		.07
555.0	557.5	75201	2.5	.0	2E41	4.75	.27	2.51	3.95	16.50					1	35	36	.45		.02
557.5	560.0	75202	2.5	.0	2F0	4.73	.19	2.80	5.17	19.00					1	35	36	.10		.02
560.0	562.5	75203	2.5	.0	2F0	4.62	.27	2.78	4.46	16.20					1	35	36	.10		.01
562.5	565.0	75204	2.5	.0	2F4	4.86	.07	3.51	6.69	21.20					1	33	35	.10		.01
565.0	567.5	75205	2.5	.0	2E41	4.74	.06	6.12	10.20	26.40					2	29	31	.10		.02
567.5	570.0	75206	2.5	.0	2E41	4.25	.05	3.75	8.24	14.90					2	26	28	.10		.02
570.0	572.5	75207	2.5	.0	2E48	4.35	.44	2.05	4.46	13.40					3	35	39	.34		.09
572.5	575.0	75208	2.5	.0	2E48	4.41	.40	1.20	3.99	12.10					5	31	36	.34		.17
575.0	577.0	75209	2.0	.0	2F9	4.94	.39	1.18	3.91	12.40					5	30	36	.22		.17
577.0	579.0	75210	2.0	.0	2D30	4.86	.12	2.14	4.13	11.80					1	38	39	.10		
579.0	581.5	75211	2.5	.0	2D43	3.50	.08	3.96	7.56	15.90					1	33	34	.10		.02
581.5	584.0	75212	2.5	.0	2D43	3.93	.16	4.22	7.59	27.70					15	13	28	.10		.02
584.0	586.5	75213	2.5	.0	2D9	3.66	.33	1.70	2.39	27.10					9	15	24	.34		.02
586.5	589.0	75214	2.5	.0	2C0	3.13	.07	.96	2.72	12.80					3	9	13	.81		.04
589.0	591.5	75215	2.5	.0	2D4	2.98	.10	3.72	5.03	42.90					3	3	7	.81		.03
591.5	594.0	75216	2.5	.0	2D4	3.28	.06	7.44	10.10	131.30					4	8	13	.45		.08
594.0	596.5	75217	2.5	.0	2D0	2.89	.06	1.95	5.01	25.50					2	1	4	.57		.03
596.5	599.0	75218	2.5	.0	2A4	2.92	.04	1.28	4.60	21.50					1	1	3	1.27		.03
599.0	600.0	75219	1.0	.0	2A4	2.84	.05	1.25	3.16	24.90					1	2	4	1.04		.02
600.0	601.0	75220	1.0	.0	2A4	2.84	.05	1.25	3.16	24.90					1	2	4	1.04		.02

DDH: 81-01

---DEPTHS---				-----ASSAYS-----																
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
197.0	208.0	75223	11.0	.0 2D0 32	3.01	.11	4.65	3.90	129.90			3	4	7	.26					.07
218.0	220.5	75225	2.5	.0 2A4	2.77	.04	1.96	2.47	47.90			.21	1	1	3	.31				.01
220.5	223.0	75226	2.5	.0 2A0	2.76	.06	.84	2.07	28.60			.27	2	2	4	.34				.01
223.0	225.5	75227	2.5	.0 2A4	2.95	.11	1.94	4.03	58.20			.41	3	5	9	.23				.04
225.5	228.0	75228	2.5	.0 2A4 21	3.07	.11	1.86	4.43	54.40			.14	4	7	11	.32				.03
228.0	232.2	75229	4.2	.0 2A4	2.92	.16	1.81	4.81	54.40			1.03	3	6	9	.35				.02
232.2	233.4	75230	1.2	.0 2D0	2.94	.09	2.37	4.34	59.40			1.10	4	3	8	.27				.04
233.4	238.4	75231	5.0	.0 2A4	2.86	.07	2.00	4.71	64.10			.27	3	3	7	.32				.02
238.4	243.0	75232	4.6	.0 2A4	2.88	.06	1.82	4.60	56.60			1.17	3	3	6	.34				.02
243.0	248.0	75233	5.0	.0 2A4 21	2.67	.04	1.23	2.78	25.20			.27	1	1	3	.37				
248.0	251.6	75234	3.6	.0 2A4	2.58	.05	1.86	2.67	31.40			.41	1	1	3	.36				
251.6	256.6	75235	5.0	.0 2A0	2.82	.10	.46	.65	16.80			.27	3	4	8	.20				.01
256.6	261.5	75236	4.9	.0 2A4 21	2.80	.06	2.10	2.33	36.10			.21	2	2	4	.29				.03
261.5	266.0	75237	4.5	.0 2B0	2.85	.20	.16	.26	6.50			1.17	4	6	11	.20				.06

DDH: 81-02

---DEPTHS---				---ASSAYS---																	
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %	S.G. W.R.	
276.0	277.2	75242	1.2	.0 2AF	3.46	.13	1.29	2.99	20.50												
277.2	279.0	75243	1.8	.0 2F4	4.36	.08	4.83	6.22	63.40												
279.0	282.0	75244	3.0	.0 2B0	2.92	.13	.52	2.19	12.40												
282.0	284.3	75245	2.3	.0 2E4	4.23	.33	2.79	3.55	44.80												
284.3	287.3	75246	3.0	.0 2F0	4.52	.23	2.38	2.73	23.00												
287.3	290.1	75247	2.8	.0 2F0	4.41	.23	3.33	4.88	36.10												
290.1	293.0	75248	2.9	.0 2A4	3.13	.24	1.98	3.68	39.80												
293.0	296.0	75249	3.0	.0 2C0	2.81	.07	.82	1.89	21.20												
296.0	299.0	75250	3.0	.0 2C0	2.82	.10	.96	2.36	27.40												
299.0	302.0	75251	3.0	.0 2C0	2.79	.09	.96	2.82	30.20												
302.0	306.0	75252	4.0	.0 2C0	2.87	.15	.74	2.67	32.70												
306.0	308.0	75253	2.0	.0 2C0	2.87	.08	.73	1.61	28.90												
308.0	312.0	75254	4.0	.0 2A0	2.88	.08	.96	1.92	27.40												
312.0	316.0	75255	4.0	.0 2A0	2.73	.05	.84	1.87	20.50												
316.0	320.0	75256	4.0	.0 2A0	2.67	.04	.46	1.35	13.10												
320.0	324.5	75257	4.5	.0 2A0	2.79	.10	1.00	1.81	31.70												

Handwritten notes: 12.9, 0.20, 2.57, 3.30, 3.00

DDH: 81-03

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													S.G. W.R.	
FROM	TO						CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %		Ba %
292.6	295.3	75261	2.7	.0	2D4	3.45	.07	4.69	8.50	43.90		.34	4	10	15	.17		.11			
295.3	299.3	75262	4.0	.0	2D0	2.93 ²³	.10	1.34	3.01	31.40		.07	3	4	8	.56		.08			
299.3	303.0	75263	3.7	.0	2C0	2.92	.08	.79	1.71	22.70		.14	3	5	8	.67		.05			
303.0	307.0	75264	4.0	.0	2C0	2.80 ⁴⁰	.04	.72	1.56	22.10		.27	2	1	4	.79		.04			
310.0	311.0	75266	1.0	.0	2F0	4.10	.20	3.38	4.23	53.50		.07	8	16	25	.34		.13			
311.0	314.0	75267	3.0	.0	1D49	2.86	.07	.20	1.03	10.00		.07	3	3	7	.90		.06			
337.0	338.0	75271	1.0	.0	1D49	3.49	.20	6.42	1.51	125.60		.07	8	10	18	.28		.05			

DDH: 81-04

Include Waste

Include Waste

---DEPTHS---				-----ASSAYS-----																
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
184.1	185.4	75275	1.3	.0 2F4	4.10	.11	7.89	8.87	150.80		.75	7	16	24	.31		.20			
190.8	192.0	75277	1.2	.0 2D4	3.21	.29	6.07	7.96	126.90		.55	4	7	11	.24		.13			
192.0	194.7	75278	2.7	.0 2F4	4.25	.27	6.86	7.43	130.90		.27	10	17	28	.38		.37			
194.7	195.6	75279	.9	.0 2BC	3.06	.35	2.74	2.52	51.60		.62	5	7	13	2.05		.14			
197.3	200.3	75281	3.0	.0 2DG	3.19	.26	2.81	2.56	50.10		.07	5	6	11	8.58		.16			
200.3	201.6	75282	1.3	.0 2BC	2.84	.04	.57	.97	10.60		.07	2	2	4	8.25		.06			
201.6	204.0	75283	2.4	.0 2L19	2.97	.07	3.48	2.59	98.30		2.47	2	5	7	3.87		.10			
204.0	205.4	75284	1.4	.0 2L19	3.37	.09	7.64	7.34	130.00		.07	6	8	15	.40		.18			
205.4	208.0	75285	2.6	.0 2C0	2.93	.07	.71	1.79	16.20		.07	4	6	10	.92		.03			
208.0	210.5	75286	2.5	.0 2C0	2.73	.03	.82	1.94	17.10		.07	1	2	3	.80		.01			
210.5	214.5	75287	4.0	.0 2C0	2.75	.03	.86	1.48	11.80		.07	1	1	3	2.25		.03			
223.0	226.8	75289	3.8	.0 2EF	4.20	.42	3.72	4.33	56.30		.07	15	18	33	.24		.11			
226.8	228.8	75290	2.0	.0 2F4	4.13	.33	5.74	9.22	81.80		.07	10	16	26	.45		.12			
230.0	235.0	75292	5.0	.0 2A0	2.73	.09	1.79	1.56	32.30		.41	3	3	7	.98		.02			
235.0	241.5	75293	6.5	.0 2A0	2.74	.05	.59	.88	13.70		.34	3	2	6	.56		.05			
241.5	245.2	75294	3.7	.0 2C0	2.81	.06	1.00	1.61	19.90		.48	2	3	6	.90		.02			
245.2	248.2	75295	3.0	.0 2A0	2.98	.11	.95	1.63	24.90		.55	9	4	14	.67		.06			
248.2	251.8	75296	3.6	.0 2A0	3.01	.09	.79	1.52	12.40		.48	5	6	12	.70		.01			
251.8	255.1	75297	3.3	.0 2A0	2.73	.04	.95	1.47	26.40		.07	2	1	3	1.05					
255.1	258.6	75298	3.5	.0 2C0	2.88	.14	1.43	2.11	64.40		.75	3	3	7	.90		.04			
258.6	262.4	75299	3.8	.0 2C0	2.93	.11	2.48	2.82	93.90		.07	4	4	8	.23		.05			
262.4	264.0	75300	1.6	.0 2A0	2.76	.09	.91	1.76	45.10		.27	4	2	6	.88		.04			
264.0	270.2	75301	6.2	.0 2A0	2.78	.13	.56	1.47	24.30		.48	3	3	6	.29		.03			

DDH: 81-05

---DEPTHS---				-----ASSAYS-----																
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
134.9	138.2	75306	3.3	.0 2D4	3.51	.12	5.76	11.80	64.10		.41	3	11	14	.21		.04			
138.2	140.5	75307	2.3	.0 2F4	4.30	.11	6.83	8.77	265.30		.34	6	19	25	.17		.27			
140.5	144.5	75308	4.0	.0 2D0	2.85	.07	2.29	3.93	49.80		.07	3	2	5	.67		.10			
144.5	146.8	75309	2.3	.0 2B0	2.63	.03	.63	2.28	18.40		.21	1		1	1.12		.01			
146.8	150.0	75310	3.2	.0 2A0	2.69	.03	1.04	2.48	20.80		.07	1		1	1.04		.01			
150.0	153.0	75311	3.0	.0 2A0	2.71	.03	1.52	2.12	45.40		.21	1	1	2	1.08		.01			
153.0	155.5	75312	2.5	.0 2D4	3.24	.06	11.10	6.81	348.30		.34	4	5	9	.17		.07			
155.5	158.0	75313	2.5	.0 2D4	3.02	.06	4.71	6.70	106.90		7.68	5	4	9	.06		.14			
158.0	161.0	75314	3.0	.0 2D0	2.81	.06	1.83	2.56	30.50		.07	3	4	7	.19		.05			
161.0	163.5	75315	2.5	.0 2B0	2.75	.04	.76	1.50	14.30		.48	2	2	4	.46		.04			
163.5	166.0	75316	2.5	.0 2B0	2.82	.05	.99	2.52	19.60		.41	3	3	6	.60		.05			
166.0	168.0	75317	2.0	.0 2C0	3.00	.09	.41	1.16	8.40		.48	4	7	12	.40		.06			
168.0	170.0	75318	2.0	.0 2B0	2.69	.04	.71	1.90	12.40		.07	2	1	4	.82		.02			
170.0	172.0	75319	2.0	.0 2B0	2.73	.06	.41	.30	14.00		.34	3	2	5	.43		.03			
172.0	175.3	75320	3.3	.0 2A0	2.76	.06	.55	.82	13.10		.07	2	2	5	.52		.04			

DDH: 81-06

-----DEPTHS-----							-----ASSAYS-----													
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
100.2	107.3	75325	7.1	.0 2C0	2.96	.11	.37	.45	17.40						.20		.03			
107.3	113.0	75326	5.7	.0 2D0	3.52	.16	3.35	4.63	66.60						.25		.09			
113.0	119.0	75327	6.0	.0 2EA	3.28	.06	3.37	3.82	60.30						2.43		.19			
119.0	127.3	75328	8.3	.0 2D0	3.01	.08	2.87	4.47	45.40						.42		.14			
127.3	130.0	75329	2.7	.0 2E4	4.44	.08	2.73	4.50	24.90						.18		.08			
130.0	132.8	75330	2.8	.0 2F0	4.22	.15	2.37	4.07	47.00						.27		.05			
132.8	134.1	75331	1.3	.0 2E4	4.31	.28	3.48	6.99	76.80						.10		.08			
134.1	138.0	75332	3.9	.0 2EF	4.49	.14	4.82	6.70	63.40						.27		.08			
138.0	140.4	75333	2.4	.0 2EF	4.21	.15	5.03	7.05	71.50						.20		.15			
140.4	144.1	75334	3.7	.0 2A0	2.92	.06	1.47	2.33	43.20						.84		.02			
144.1	147.4	75335	3.3	.0 2A0	2.70	.03	.50	1.07	19.00						.69					
147.4	151.5	75336	4.1	.0 2A0	2.69	.02	.85	2.31	19.00						.87		.01			
151.5	154.0	75337	2.5	.0 2A0	2.60	.04	1.02	1.79	19.30						.65					
154.0	158.7	75338	4.7	.0 2A0	2.69	.06	.69	1.25	13.70						.36					

33.1'
 2340 1.90
 8.3
 7.6

DDH: 81-07

-----DEPTHS-----				-----ASSAYS-----																	
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %	S.G. W.R.	
53.0	61.0	75342	8.0	.0 2E14	3.76 ⁴⁰	.14	3.01	5.44	56.30		.07	5	16	21	.49						.10
61.0	67.5	75343	6.5	.0 2A14	2.98	.06	1.42	4.21	24.90		1.30	4	6	10	.43						.04
67.5	76.0	75344	8.5	.0 2A1	3.00 ²¹	.10	1.07	2.78	25.80		1.23	5	6	11	1.11						.04
76.0	78.0	75345	2.0	.0 2E14	3.44	.13	1.85	5.98	31.70		.07	8	12	20	.39						.06
78.0	83.0	75346	5.0	.0 2C2	3.38	.13	1.35	1.36	22.70		.34	6	13	20	.55						.04
83.0	87.7	75347	4.7	.0 2C2	3.13 ²¹	.08	1.43	1.96	25.50		1.30	5	9	15	.47						.03
87.7	96.0	75348	8.3	.0 2C0	3.00	.08	.48	1.24	13.70		.62	7	7	14	.62						.08
96.0	103.0	75349	7.0	.0 2A0	2.80 ²¹	.06	.64	1.44	16.80		.41	7	3	10	.56						.08
103.0	106.0	75350	3.0	.0 2A/1D	2.60	.04	.86	1.92	18.70		.55	2	1	3	.34						.02

DDH: 81-08

							-----ASSAYS-----														
DEPTHS	SAMPLE	INT.	REC.	ROCK	S.G.	CU	Pb	Zn	Ag(AA)	Ag(FA)	Au(FA)	Po	Py	TOT	BAO	Hg	Mn	As	Ba	S.G.	
FROM	TO	NO.		UNIT	PULP	%	%	%	g/mT	g/mT	g/mT	%	%	Fe	%	%	%	%	%	W.R.	
174.0	176.0	75354	2.0	.0	2D4	3.45	.14	7.73	15.40	8.40		.82	6	6	13	.02					.15
176.0	178.2	75355	2.2	.0	2D4	3.46	.16	7.22	16.70	67.50		.34	6	7	13	.02					.13
178.2	180.5	75356	2.3	.0	2C3	3.52	.14	.62	1.47	14.00		.34	7	14	22	.11					.06
180.5	182.9	75357	2.4	.0	2C3	3.28	.04	.75	.59	13.40		.34	2	14	16	.24					.03
182.9	186.5	75358	3.6	.0	2D4	3.48	.10	7.34	9.85	113.50		.72	7	7	14	3.71					.17
186.5	191.0	75359	4.5	.0	1D9	2.90	.05	1.38	1.52	29.90		.34	5	4	9	4.07					.14
191.0	196.0	75360	5.0	.0	1D9	2.94	.04	1.36	1.60	28.90		.62	6	4	11	3.29					.15
196.0	198.3	75361	2.3	.0	1D4	2.90	.05	.70	.76	19.00		.62	7	6	13	3.39					.11
198.3	199.8	75362	1.5	.0	2C3	3.57	.19	1.00	1.11	28.00		.27	11	12	23	5.49					.09
199.8	201.9	75363	2.1	.0	1D4	2.95	.05	.70	.58	14.90		.34	5	4	9	12.40					.12
201.9	205.0	75364	3.1	.0	2D4	3.20	.08	3.46	7.48	68.10		.96	6	8	15	2.73					.23
205.0	209.0	75365	4.0	.0	2D0	3.81	.06	1.63	3.83	33.90		.48	3	4	7	.18					.06
209.0	213.0	75366	4.0	.0	2D0	2.85	.04	1.63	3.93	30.20		1.03	3	3	6	.40					.04
213.0	217.0	75367	4.0	.0	2D0	2.90	.05	2.47	2.86	45.40		.34	3	4	7	.13					.03
217.0	221.0	75368	4.0	.0	2D0	2.91	.05	1.54	3.37	26.10		.75	3	4	8	.36					.04
221.0	223.4	75369	2.4	.0	2F4	4.33	.12	6.06	9.34	73.70		1.65	7	19	27	.06					.08
223.4	226.8	75370	3.4	.0	2F4	4.62	.04	7.96	12.10	75.90		.55	1	22	24	.04					.02
226.8	230.8	75371	4.0	.0	2E0	4.64	.39	1.45	.84	25.80		2.33	5	27	32	.04					.18
230.8	233.4	75372	2.6	.0	2E0	4.66	.43	.28	.36	14.90		.07	5	29	34	.03					.14
233.4	235.4	75373	2.0	.0	2E1	4.39	.30	.85	.95	17.70		.07	4	27	31	.03					.15
235.4	239.0	75374	3.6	.0	2E1	4.21	.16	1.25	1.93	16.80		.07	5	21	26	.03					.24
239.0	244.1	75375	5.1	.0	2E14	4.44	.21	4.89	7.77	51.00		.07	7	19	26	.03					.21
244.1	247.0	75376	2.9	.0	2E0	4.08	.23	1.06	2.25	19.30		.34	10	18	28	.04					.29
247.0	248.3	75377	1.3	.0	2E1	3.96	.50	1.71	2.89	27.10		.14	18	12	30	.06					.09
248.3	250.0	75378	1.7	.0	2H84	4.39	.12	4.10	7.26	34.20		.07	6	19	25	.04					.18
250.0	255.5	75379	5.5	.0	2F0	3.15	.11	1.77	6.90	25.20		.27	5	6	12	.29					.10
255.5	260.5	75380	5.0	.0	2A4	2.91	.03	2.40	6.69	21.20		.07	2	3	5	.31					.03
260.5	266.7	75381	6.2	.0	2A4	2.92	.04	2.42	4.79	29.90		.69	2	3	6	.24					.03

DDH: 81-10

---DEPTHS---				-----ASSAYS-----																
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
372.0	376.8	75388	4.8	.0 2F4	4.52	.22	4.92	6.09	86.80		1.23	6	22	29	.07		.18			
376.8	378.0	75389	1.2	.0 1D4	3.28	.13	1.10	.52	41.40		.34	19	6	25	.31		.66			
378.0	381.0	75390	3.0	.0 2E7	4.43	.15	.61	.54	19.00		.07	8	25	34	.03		.19			
381.0	383.5	75391	2.5	.0 2F4	4.57	.18	.84	.74	16.20		.17	5	28	33	.04		.14			
383.5	386.0	75392	2.5	.0 ****	4.65	.12	6.21	6.02	83.40		.62	6	23	29	.05		.31			
386.0	388.5	75393	2.5	.0 2F4	4.38	.27	8.57	7.95	97.70		1.03	3	19	23	.05		.13			
388.5	391.0	75394	2.5	.0 2F0	4.56	.28	1.47	1.42	20.80		.07	6	23	29	.02		.29			
391.0	393.0	75395	2.0	.0 2F0	4.29	.27	4.36	5.38	49.50		.34	8	18	27	.02		.76			
393.0	408.0	75396	15.0	.0 2F0	4.52	.19	4.47	5.41	54.40		.07	7	21	28	.01		.42			
408.0	410.5	75397	2.5	.0 2C0	2.95	.18	.19	.55	8.70		.07	4	6	11	.32		.04			
410.5	413.0	75398	2.5	.0 2C0	3.26	.30	.31	1.17	16.50		.51	7	11	19	.10		.05			
413.0	415.5	75399	2.5	.0 2C0	3.34	.21	2.05	1.58	36.70		.07	7	11	19	.07		.06			
415.5	418.4	75400	2.9	.0 2C0	3.07	.17	.69	.30	15.60		.21	7	7	15	.19		.14			
418.4	422.0	75401	3.6	.0 2C0	2.80	.12	1.16	.61	22.10		.34	3	5	8	.40		.05			
422.0	423.6	75402	1.6	.0 2E0	3.43	.19	.38	.12	13.40		.07	6	15	22	.08		.04			
423.6	425.5	75403	1.9	.0 2C2	3.45	.20	.07	.10	14.00		.21	5	15	20	.06		.03			
425.5	427.0	75404	1.5	.0 2E4	3.96	.09	1.99	3.29	22.10		.07	6	19	25	.02		.14			
427.0	429.3	75405	2.3	.0 2E4	4.42	.10	1.88	2.87	22.70		.07	3	25	28	.02		.13			

21

DDH: 81-11

---DEPTHS---				-----ASSAYS-----																
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
286.5	288.0	75410	1.5	.0	2J4	4.12	.34	3.80	7.23	84.60	.14	12	16	28	.38		.30			
288.0	290.0	75411	2.0	.0	2H4	3.87	.35	1.92	3.14	41.70	.07	17	13	31	.02		.12			
290.0	292.5	75412	2.5	.0	2H4	4.21	.50	2.42	5.24	56.30		21	12	34	.04		.22			
302.0	304.0	75414	2.0	.0	2L1	3.10	.26	.88	1.13	27.10	.07	6	7	13	.24		.06			
304.0	309.5	75415	5.5	.0	2C7	3.38	.08	.26	1.04	20.20	.07	2	13	15	.17		.05			
309.5	313.0	75416	3.5	.0	2C7	3.53	.04	1.02	2.41	21.80	.14		14	15	.14		.02			
313.0	314.0	75417	1.0	.0	2F4	4.57	.01	3.52	7.87	37.30	.01		23	24	.14		.03			
314.0	318.0	75418	4.0	.0	2E4	4.42	.08	7.32	11.70	67.80	.07		19	19	.58		.04			
318.0	319.7	75419	1.7	.0	2F4	3.85	.11	2.39	11.60	44.50		2	15	18	3.44		.09			
319.7	321.4	75420	1.7	.0	2L4	3.13	.05	5.96	2.84	51.60		2	6	8	11.85		.08			
342.0	346.0	75422	4.0	.0	2E4	4.36	.34	2.04	2.35	47.00		6	26	33	.13		.21			
346.0	348.0	75423	2.0	.0	2E4	4.56	.17	4.76	4.48	74.60	.07	5	24	29	.06		.21			
357.0	359.5	75425	2.5	.0	2E4	3.76	.30	4.93	2.65	76.20	.07	7	16	23	.20		.14			
359.5	362.0	75426	2.5	.0	2E4	4.02	.15	3.32	1.66	64.40	.07	9	18	28	.10		.16			
362.0	365.5	75427	3.5	.0	2E0	4.58	.14	.89	1.15	19.30	.07	7	25	32	.06		.32			
365.5	369.0	75428	3.5	.0	2E0	4.63	.09	.48	.57	22.10	.07	6	28	34	.04		.25			
369.0	372.5	75429	3.5	.0	2E1	4.12	.36	.89	.55	22.40	.07	3	34	38	.04		.08			
372.5	376.0	75430	3.5	.0	2E1	4.08	.59	1.78	1.83	28.30	.07	3	23	26	.05		.07			
376.0	378.5	75431	2.5	.0	2E14	4.48	.17	2.80	1.42	47.90	.07	6	24	31	.03		.12			
378.5	381.0	75432	2.5	.0	2E1	4.54	.09	.88	.53	18.40	.17	1	29	31	.04		.04			
381.0	384.7	75433	3.7	.0	2E0	4.15	.12	1.32	.73	30.20	.07	4	23	27	.06		.14			
384.7	387.6	75434	2.9	.0	2E0	3.75	.22	.53	1.40	31.10	.07	12	17	29	.08		.20			
387.6	390.4	75435	2.8	.0	2H14	3.92	.12	3.72	3.38	53.80	.07	11	16	27	.05		.11			
390.4	392.0	75436	1.6	.0	1D/2H	3.38	.21	1.58	2.68	25.80	.17	12	9	22	.13		.11			
392.0	395.8	75437	3.8	.0	2H4	4.06	.36	4.45	4.09	44.20	.07	12	16	28	.06		.06			
395.8	397.0	75438	1.2	.0	2F0	4.39	.17	4.04	5.30	37.90	.07	7	19	27	.05		.26			
397.0	400.7	75439	3.7	.0	2F4	3.57	.47	3.64	8.00	36.10	.07	5	19	25	.03		.23			
400.7	404.2	75440	3.5	.0	2C2	4.22	.36	.45	1.83	19.00	.07	7	12	20	.06		.11			
404.2	407.7	75441	3.5	.0	2F0	4.13	.26	2.90	4.90	20.20	.07	6	18	24	.03		.19			
407.7	411.2	75442	3.5	.0	2C2	3.95	.20	1.28	2.14	13.10	.07	7	16	24	.04		.37			
411.2	415.3	75443	4.1	.0	2C2	3.93	.29	.58	1.49	13.70	.07	5	18	23	.03		.15			
415.3	418.4	75444	3.1	.0	2E1	3.92	.40	.29	.51	12.10	.07	3	21	24	.07		.08			
418.4	419.9	75445	1.5	.0	2E0	3.31	.14	.44	1.04	7.50	.14	3	13	16	.22		.04			
419.9	423.9	75446	4.0	.0	2F4	4.37	.11	3.50	9.47	23.60	.07	2	23	26	.01		.07			
423.9	427.8	75447	3.9	.0	2F4	4.26	.14	6.45	12.90	36.70	.07	3	19	23	.02		.06			
427.8	429.5	75448	1.7	.0	2F4	4.31	.08	5.05	10.47	29.20	.07	3	19	23	.01		.05			
429.5	433.0	75449	3.5	.0	2F4	3.58	.04	5.02	10.80	35.50	.07	2	13	15	.06		.04			
433.0	437.5	75450	4.5	.0	2F4	3.71	.04	4.84	9.63	37.30	.07	1	16	18	.05		.03			
437.5	438.7	75451	1.2	.0	2F4	4.29	.15	4.05	8.25	26.80	.07	7	21	28	.03		.14			
438.7	440.7	75452	2.0	.0	2F4	4.35	.03	5.68	12.50	39.80	.07	2	21	23	.03		.04			
440.7	442.0	75453	1.3	.0	2D4	3.90	.02	9.70	12.60	47.60	.07	2	15	17	.05		.03			
442.0	445.0	75454	3.0	.0	2F4	4.47	.03	6.18	10.70	33.60	.07	2	23	25	.03		.03			
445.0	448.0	75455	3.0	.0	2F4	3.50	.06	2.82	8.68	25.80	.07	2	14	17	.07		.03			
448.0	451.7	75456	3.7	.0	2FA	3.49	.07	1.64	7.04	23.60	.07	2	15	17	.05		.02			
451.7	456.8	75457	5.1	.0	2FA	3.46	.08	2.14	7.87	24.90	.07	2	14	17	.04		.02			
456.8	460.8	75458	4.0	.0	2FA	3.83	.05	4.30	7.59	31.10	.07	2	18	21	.02		.02			
460.8	463.5	75459	2.7	.0	2FA	3.51	.13	7.79	15.70	55.70	.17	4	8	13	.06		.02			

Waste

Waste

Waste

Waste

33

60

Waste

Waste

40

40

50

40

50

50

21

DDH: 81-12

---DEPTHS---				---ASSAYS---																
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe %	BAO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
206.3	208.0	75462	1.7	.0	2C7	3.12	.20	.17	.18	7.80		.07	6	12	18	.10				.04
208.0	213.2	75463	5.2	.0	2C7	3.18	.28	.37	.62	10.00		.07	7	11	19	2.27				.05
<i>Include whole</i> → 213.2	214.9	75464	1.7	.0	2F0	4.30	<i>23</i> .04	5.60	8.38	52.30		.07	2	26	29	2.34				.05
218.0	219.6	75466	1.6	.0	2F7	4.32	.12	8.32	7.81	118.50		.17	7	11	19	19.50				.37
<i>Waste</i> → 219.6	221.2	75467	1.6	.0	2E7	3.96	.11	8.73	8.38	126.00		.17	5	17	22	3.91				.26
262.0	264.6	75470	2.6	.0	2H4	4.11	.28	4.20	6.25	50.10		.07	13	20	34	.20				.19
264.6	267.0	75471	2.4	.0	2E4	4.29	<i>50</i> .27	6.22	9.28	80.90		.07	15	19	34	.02				.18
267.0	277.0	75472	10.0	.0	2E4	4.32	.24	5.50	8.47	73.70		.07	14	21	35	.01				.13
277.0	278.0	75473	1.0	.0	2F4	4.67	.08	7.86	13.70	81.50		.07	3	27	30	.01				.04
278.0	282.0	75474	4.0	.0	2E4	4.45	.29	2.50	4.53	35.50		.07	9	29	39	.01				.14
282.0	287.0	75475	5.0	.0	2E4	4.35	<i>50</i> .34	2.71	5.15	37.30		.07	14	25	39	.01				.14
287.0	292.0	75476	5.0	.0	2D0	3.23	.10	2.15	4.22	32.00		.07	6	10	16	.16				.07
292.0	299.8	75477	7.8	.0	2D0	3.52	.21	2.32	3.54	34.50		.07	8	16	24	.07				.08
299.8	301.1	75478	1.3	.0	2E7	3.71	.22	.57	1.86	17.10		.07	9	23	32	.06				.06
301.1	303.9	75479	2.8	.0	2A4	3.24	.11	1.96	4.67	34.20		.07	7	10	17	.17				.14
303.9	309.5	75480	5.6	.0	2H1	3.57	.26	1.75	6.28	27.70		.07	7	16	24	.06				.07
309.5	314.0	75481	4.5	.0	2F4	4.58	<i>70</i> .16	5.34	8.67	42.90		.07	4	29	33	.02				.19
314.0	318.0	75482	4.0	.0	2E1	3.91	.18	1.30	2.32	19.30		.07	4	27	31	.02				.16
318.0	322.0	75483	4.0	.0	2E1	4.00	.14	.83	2.36	12.10		.07	4	28	33	.01				.18
322.0	325.0	75484	3.0	.0	2E4	3.94	.17	2.13	2.69	16.80		.07	5	25	30	.06				.15
325.0	328.0	75485	3.0	.0	2D4	2.98	.11	2.70	7.93	23.60		.07	3	3	6	.23				.03
328.0	332.5	75486	4.5	.0	2A4	2.96	<i>21</i> .07	1.11	4.49	27.40		.48	3	5	9	.24				.01
332.5	337.0	75487	4.5	.0	2C0	2.94	.09	.94	2.82	23.30		.07	4	5	9	.21				.03
337.0	342.0	75488	5.0	.0	2D0	2.96	.05	2.79	5.16	27.70		.17	3	4	7	.04				.02
342.0	347.0	75489	5.0	.0	2D0	2.92	.04	2.45	3.94	25.20		.14	3	3	6	.20				.02
347.0	350.0	75490	3.0	.0	2C0	2.90	.07	1.59	1.97	16.20		.07	3	4	8	.21				.03
350.0	354.9	75491	4.9	.0	2D4	3.10	<i>21</i> .06	5.97	4.19	67.50		.21	4	5	10	.14				.03
354.9	360.7	75492	5.8	.0	2D4	3.23	.06	7.90	6.47	65.30		.21	5	5	10	.18				.08
360.7	362.3	75493	1.6	.0	2D4	3.39	.13	5.11	13.40	54.10		.82	6	7	13	.13				.04
362.3	366.7	75494	4.4	.0	2A4	2.93	.04	1.90	4.94	21.80		.69	3	3	7	.24				.01
366.7	370.0	75495	3.3	.0	2D0	2.98	.03	3.02	5.78	31.40		.89	5	3	8	.10				.04
370.0	374.0	75496	4.0	.0	2D7	3.08	<i>21</i> .06	2.52	4.95	29.50		.82	6	6	12	.22				.05
374.0	379.5	75497	5.5	.0	2D7	3.02	.05	3.43	4.84	39.80		.75	4	5	9	.09				.03
379.5	385.0	75498	5.5	.0	2E4	3.92	.18	6.74	14.00	79.90		.07	6	17	23	.04				.04
385.0	390.0	75499	5.0	.0	2A4	3.02	.01	2.05	8.31	19.30		.84	2	5	8	.24				.02
390.0	394.0	75500	4.0	.0	2A4	2.91	<i>21</i> .02	2.54	4.60	19.60		.69	1	4	6	.18				.02
394.0	396.4	75501	2.4	.0	2A4	2.91	.06	2.27	5.14	20.20		.07	3	11	14	.23				.02
396.4	400.0	75502	3.6	.0	2D4	3.38	.09	5.67	11.90	35.50		.07	6		6	.08				.03
400.0	405.0	75503	5.0	.0	2A4	2.84	.02	2.49	5.05	22.10		.34	2	2	5	.25				.02
405.0	410.0	75504	5.0	.0	2A4	3.19	<i>21</i> .10	1.70	4.98	23.60		.27	6	10	16	.08				.03
410.0	415.0	75505	5.0	.0	2A4	3.27	.10	1.48	3.83	21.80		.07	5	13	19	.06				.03
415.0	420.0	75506	5.0	.0	2A0	2.98	.12	1.34	1.99	18.40		.07	4	7	11	.14				.02
420.0	424.1	75507	4.1	.0	2A0	2.99	<i>21</i> .09	.82	1.23	15.60		.62	3	5	8	.18				.01
<i>Waste</i> → 424.1	428.2	75508	4.1	.0	2C0	3.07	.17	.41	2.78	9.30		.17	7	8	15	.09				.06
444.9	447.0	75510	2.1	.0	0Q9	3.73	<i>Waste</i> .40	29.90	3.47	344.60		.96	3	3	6	.08				.05
447.0	452.4	75511	5.4	.0	2D7	3.27	<i>21</i> .39	3.89	4.68	41.10		.07	4	12	16	.09				.02

DDH: 81-13

---DEPTHS---				-----ASSAYS-----																
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
330.9	336.2	75515	5.3	.0 2E4	4.33	24	7.18	8.17	97.70						.07	13	21	34		.17
336.2	340.0	75516	3.8	.0 2E0	4.71	11	2.24	1.67	24.60						.07	4	37	42		.10
340.0	344.8	75517	4.8	.0 2E4	4.72	24	2.80	2.60	27.10						.07	4	34	39		.10
344.8	348.0	75518	3.2	.0 2F4	4.65	21	4.29	6.08	32.70						.07	4	33	38	.01	.06
348.0	351.0	75519	3.0	.0 2F4	4.75	15	5.04	5.89	37.00						.07	2	36	38	.02	.04
351.0	356.0	75520	5.0	.0 2E4	4.66	08	3.48	3.99	35.50						.07	3	35	38	.08	.06
356.0	358.0	75521	2.0	.0 2JF	4.21	17	2.50	6.15	38.30						.07	7	26	34	.09	.12
358.0	360.0	75522	2.0	.0 2AC	3.00	12	.97	1.85	24.30						.07	5	6	11	.31	.08
360.0	364.0	75523	4.0	.0 2A0	2.80	09	.93	2.15	20.80						.07	2	3	6	.27	.02
364.0	369.0	75524	5.0	.0 2A4	2.72	04	1.35	3.26	16.80						.07	1	1	3	2.01	.03
417.0	423.0	75527	6.0	.0 2A4	3.09	12	2.34	4.25	51.00						.41	5	6	12	.20	.04
423.0	425.4	75528	2.4	.0 2A3	3.03	10	.77	2.63	28.90						.82	5	7	12	.22	.03
425.4	428.0	75529	2.6	.0 2A0	2.85	05	1.15	2.26	21.10						.07	3	3	7	.22	.03
428.0	434.0	75530	6.0	.0 2A0	2.71	06	1.34	1.97	14.60						.07	1	2	3	.23	.01
434.0	440.0	75531	6.0	.0 2A4	2.81	09	2.84	3.88	26.10						.07	2		2	.13	.02
440.0	445.0	75532	5.0	.0 2A4	2.91	12	2.03	4.22	30.80						.07	3	2	6	.11	.02
445.0	450.0	75533	5.0	.0 2A4	2.79	09	1.62	3.57	23.00						.14	3	3	6	.14	.03

Waste

23.11
0.17, 4.11, 4.85, 4.69

DDH: 81-14

---DEPTHS---					-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe %	BAO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
336.7	341.0	75538	4.3	.0 2C0	2.80	.10	.18	.13	8.40		.07	3	4	8	.36		.03			
341.0	346.0	75539	5.0	.0 2C0	2.86	.10	.13	.07	7.50		.07	4	6	10	.17		.03			
346.0	351.0	75540	5.0	.0 2C0	3.03	2319	.10	.29	10.00		.07	5	10	15	.14		.05			
351.0	356.0	75541	5.0	.0 2C0	3.11	24	.22	.19	16.50		.07	4	12	17	.07		.05			
356.0	361.0	75542	5.0	.0 2C0	3.23	.27	.17	1.17	19.60		.07	5	14	20	.05		.12			
361.0	367.2	75543	6.2	.0 2C3	3.18	2317	.10	.44	11.20		.07	4	14	18	.09		.04			
367.2	370.5	75544	3.3	.0 2A3	3.30	.13	.08	.22	8.10		.07	3	18	22	.05		.02			
370.5	373.5	75545	3.0	.0 2F4	3.63	.10	1.98	10.70	30.80		.07	3	17	21	.03		.07			
373.5	376.0	75546	2.5	.0 2F4	3.59	.04	4.43	9.50	52.30		.17	3	16	19	.09		.03			
376.0	379.3	75547	3.3	.0 2E1	3.75	50.03	.37	2.32	12.80		.07	2	27	29	.11		.03			
379.3	382.3	75548	3.0	.0 2F4	3.82	.04	3.27	7.80	35.80		.07	2	24	26	.07		.01			
383.1	388.2	75550	5.1	.0 2C3	3.73	.09	.09	.06	8.70		.27	1	28	29	.07		.01			
389.5	392.5	75552	3.0	.0 2C3	3.70	50.14	.58	2.55	13.10		.41		27	27	.10		.01			
392.5	395.0	75553	2.5	.0 2F4	4.31	.05	5.33	8.63	62.20		.14	1	28	30	3.98		.05			
414.0	417.0	75555	3.0	.0 2F0	4.43	Waste	3.96	2.37	110.40		.21	6	31	38	.17		.25			
434.6	435.9	75558	1.3	.0 2F0	4.16	.35	1.68	2.40	32.70		.27	5	29	35	2.10		.08			
435.9	440.0	75559	4.1	.0 2G4	4.59	.05	6.57	9.14	92.40		.07	2	12	15	33.80		.05			
440.0	445.0	75560	5.0	.0 2G4	4.51	60.06	5.51	8.26	76.20		.07	2	14	16	32.95		.07			
445.0	450.0	75561	5.0	.0 2G4	4.43	.06	6.26	10.19	89.30		.07	2	9	11	38.26		.05			
450.0	454.0	75562	4.0	.0 2G4	4.52	.05	6.08	9.28	90.20		.07	1	9	11	44.12		.03			
454.0	457.0	75563	3.0	.0 2G4	4.46	60.04	5.64	9.24	92.70		.07	1	8	10	42.69		.03			
457.0	460.0	75564	3.0	.0 2I7	3.97	.29	2.85	1.80	53.80		.07	11	24	35	2.01		.17			
465.5	467.8	75566	2.3	.0 2E0	4.40	.21	.84	1.00	40.40		.07	9	31	41	2.80		.13			
470.0	474.4	75568	4.4	.0 2H9	4.08	.29	.35	1.40	25.20		.07	26	17	44	.04		.04			
474.4	479.3	75569	4.9	.0 2H4	4.28	70.32	3.47	7.32	53.80		.48	28	13	41	.07		.06			
479.3	482.3	75570	3.0	.0 2E7	3.65	.22	.08	.82	12.40		.17	10	28	39	.03		.07			
482.3	485.0	75571	2.7	.0 2H9	4.03	.22	.58	2.10	23.90		.41	26	16	42	.03		.04			
485.0	488.0	75572	3.0	.0 2C7	3.59	.08	.09	.15	6.80		.21	5	23	29	.03		.03			
488.0	491.2	75573	3.2	.0 2C7	3.38	.14	.09	.27	10.00		.27	15	12	28	.02		.02			
491.2	496.2	75574	5.0	.0 2H9	4.05	.20	1.06	3.28	24.30		.14	34	8	43	.02		.02			
496.2	500.2	75575	4.0	.0 2D3	3.72	70.15	1.76	2.80	28.60		.27	8	21	29	.06		.11			
500.2	504.5	75576	4.3	.0 2C3	3.51	.35	1.29	1.04	31.70		.07	5	20	26	.03		.09			
504.5	508.0	75577	3.5	.0 2H9	3.96	.32	1.44	3.55	34.50		.07	27	11	39	.02		.06			
508.0	511.0	75578	3.0	.0 2C3	3.83	.32	.69	.83	16.20		.07	4	27	31	.03		.14			
511.0	516.0	75579	5.0	.0 2C3	3.65	.27	.05	.57	13.40		.24	2	26	28	.04		.03			
516.0	521.0	75580	5.0	.0 2C3	3.81	50.26	.06	.49	7.80		.07	1	29	30	.05		.03			
521.0	525.0	75581	4.0	.0 2C3	3.89	50.22	.89	1.82	13.70		.07	3	27	31	.05		.13			
525.0	528.0	75582	3.0	.0 2C3	3.65	.22	.10	.54	10.00		.07	2	26	28	.05		.04			
528.0	532.0	75583	4.0	.0 2F4	4.04	.10	4.31	9.83	27.10		.07	3	24	28	.20		.08			
532.0	536.0	75584	4.0	.0 2F4	4.52	.03	5.82	11.20	37.00		.07	2	30	32	.05		.03			
536.0	540.0	75585	4.0	.0 2F4	4.37	50.06	7.17	13.90	33.30		.07	3	26	29	.04		.04			
540.0	543.4	75586	3.4	.0 2F4	4.59	.01	6.29	12.50	35.50		.14	1	30	32	.04		.02			
543.4	544.4	75587	1.0	.0 2F4	3.68	.01	3.95	13.00	24.30		.07	1	18	19	.15		.01			
544.4	549.0	75588	4.6	.0 2F4	4.50	50.03	7.48	15.50	39.50		.41	2	26	29	.05		.03			
549.0	554.0	75589	5.0	.0 2F4	4.39	.04	7.13	13.50	39.80		.07	2	26	29	.04		.02			
554.0	559.0	75590	5.0	.0 2D3	3.40	.06	.57	3.81	10.00		.07	2	26	29	.11		.03			
559.0	564.0	75591	5.0	.0 2A3	3.52	.02	.46	1.69	13.10		.07	1	21	23	.10		.02			
564.0	569.0	75592	5.0	.0 2A3	3.39	21.03	.06	.35	3.70		.07	1	21	22	.10		.01			
569.0	572.4	75593	3.4	.0 2A34	3.41	.26	2.43	6.34	26.10		.51	5	15	20	.06		.05			

Include Waste

Waste

Include Waste

DDH: 81-15

---DEPTHS---				-----ASSAYS-----																
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
477.5	482.0	75598	4.5	.0	2D0	3.95	.08	5.33	8.69	50.70		.41	3	22	25	.70				.05
482.0	485.7	75599	3.7	.0	2D0	3.72	.03	2.60	6.75	26.40		.27	1	21	23	.91				.02
485.7	488.0	75600	2.3	.0	2CE	3.74	.06	2.02	2.81	34.80		.48	4	19	23	5.33				.10
488.0	491.4	75601	3.4	.0	2CE4	3.37	.12	1.76	1.98	25.80		.62	6	15	21	.22				.14
493.2	497.0	75603	3.8	.0	2CE4	3.65	.12	2.34	3.53	44.50		1.20	3	16	19	8.71				.10
497.0	500.7	75604	3.7	.0	2CE	3.22	.17	1.01	1.00	20.80		1.23	3	14	18	.29				.06
500.7	503.7	75605	3.0	.0	2EF	3.76	.15	2.75	3.78	27.70		.07	19	19	.07					.18
503.7	506.6	75606	2.9	.0	2EF	3.91	.14	4.92	6.85	41.10		.17	8	20	29	.06				.12
506.6	510.0	75607	3.4	.0	2DE	3.43	.11	3.63	6.45	40.70		.27	8	13	21	.20				.11
510.0	516.0	75608	6.0	.0	2CE	3.33	.16	.60	3.18	16.20		.51	6	16	23	.23				.08
516.0	521.0	75609	5.0	.0	2DE	3.96	.26	2.40	3.21	30.50		.07	5	25	31	.01				.19
521.0	526.0	75610	5.0	.0	2DE	4.29	.25	4.00	4.94	35.10		.07	6	28	34	.01				.25
526.0	530.0	75611	4.0	.0	2CE	3.64	.23	.45	1.08	12.80		.07	4	23	28	.01				.18
530.0	533.0	75612	3.0	.0	2CE	3.46	.22	.98	2.17	10.90		.17	5	19	24	.04				.16
533.0	534.0	75613	1.0	.0	1D9	3.47	.07	.95	3.11	19.30		.07	2	19	21	.08				.06
534.0	537.0	75614	3.0	.0	2E1	3.87	.18	.69	1.73	10.30		.17	3	27	31	.02				.11
537.0	540.0	75615	3.0	.0	2E1	4.05	.33	.41	1.69	13.10		.27	5	29	34	.01				.17
540.0	542.0	75616	2.0	.0	2C9	3.50	.43	.80	1.75	13.40		.27	4	21	25	.01				.10
542.0	545.3	75617	3.3	.0	2EF	4.27	.09	4.20	8.49	19.00		.14	4	28	32	.01				.08
545.3	547.7	75618	2.4	.0	2EF	4.18	.05	4.95	12.00	18.00		.07	3	24	27	.06				.04
547.7	552.0	75619	4.3	.0	2EF	3.49	.08	5.54	10.70	33.00		.07	3	12	15	.06				.04
552.0	555.6	75620	3.6	.0	2F4	4.59	.02	6.72	10.40	30.20		.07	2	31	33	.03				.02

DDH: 81-16

					-----ASSAYS-----															
---DEPTHS---	SAMPLE INT. REC. ROCK S.G.	NO.	UNIT	PULP	CU	Pb	Zn	Ag(AA)	Ag(FA)	Au(FA)	Po	Py	TOT	BAO	Hg	Mn	As	Ba	S.G.	
FROM TO					%	%	%	g/mT	g/mT	g/mT	%	%	Fe	%	%	%	%	%	W.R.	
218.7	220.6	75626	1.9	.0	2D4	3.30	.53	5.72	4.59	235.10			15	.70						.10
220.6	222.5	75627	1.9	.0	2E4	3.70	.57	1.50	4.57	65.90			29	.63						.10
222.5	224.6	75628	2.1	.0	2D0	3.73	.15	1.09	4.35	33.30			26	.07						.04
224.6	226.7	75629	2.1	.0	2D4	3.71	.13	3.64	8.59	74.30			23	.16						.15
226.7	228.8	75630	2.1	.0	2D0	3.60	.09	1.65	4.52	38.60			24	.03						.06
228.8	231.3	75631	2.5	.0	2E4	3.86	.21	8.33	12.40	84.60			22	.07						.39
231.3	233.4	75632	2.1	.0	2D0	3.72	.19	2.10	6.32	32.00			25	.04						.13
233.4	234.5	75633	1.1	.0	2F0	3.85	.04	2.36	5.69	32.70			26	.02						.01
234.5	236.9	75634	2.4	.0	2D0	3.76	.04	1.65	6.47	23.90			25	.01						.02
236.9	239.3	75635	2.4	.0	2D0	3.76	.07	3.39	5.99	63.10			24	.06						.03
239.3	243.5	75636	4.2	.0	2EF/4	4.38	.17	7.56	5.58	163.60			32	.03						.15
252.6	253.3	75638	.7	.0	2E0	3.98	.27	.17	.38	13.70			34	.42						.16
254.8	257.3	75640	2.5	.0	2E8	4.54	.20	1.03	.30	33.60			41	.04						.32
257.3	259.8	75641	2.5	.0	2E8	4.45	.23	.69	.32	29.50			41	.04						.20
259.8	262.3	75642	2.5	.0	2E8	4.40	.16	1.02	.36	30.80			40	.04						.27
262.3	264.8	75643	2.5	.0	2E8	4.56	.22	1.34	.88	48.50			40	.02						.34
264.8	267.3	75644	2.5	.0	2E84	4.59	.27	2.99	2.41	84.30			40	.06						.39
267.3	269.8	75645	2.5	.0	2E8	4.52	.14	2.39	1.45	55.10			40	.04						.36
269.8	272.3	75646	2.5	.0	2E8	4.45	.10	.05	.17	8.40			41	.07						.22
272.3	274.8	75647	2.5	.0	2E8	4.42	.10	.04	.15	6.20			41	.05						.25
274.8	277.3	75648	2.5	.0	2E8	4.43	.23	1.21	.20	35.50			40	.07						.36
277.3	279.4	75649	2.1	.0	2H9	4.15	.77	.61	.15	22.10			52	.07						.20
279.4	281.4	75650	2.0	.0	2H4	4.33	.77	3.10	2.89	85.80			8	.06						.35
281.4	283.4	75651	2.0	.0	2C2	4.31	.25	.24	.16	13.40			44	.07						.20
283.4	286.2	75652	2.8	.0	2E8	4.43	.16	.14	.22	17.40			40	.08						.20
286.2	289.0	75653	2.8	.0	2E84	4.56	.20	3.17	2.67	52.60			39	.01						.39
289.0	291.8	75654	2.8	.0	2E8	4.50	.28	.80	.29	63.40			41	.02						.38
291.8	294.5	75655	2.7	.0	2E8	4.48	.13	1.58	1.17	70.30			39	.02						.36
294.5	296.7	75656	2.2	.0	2F4	4.45	.36	8.15	5.82	143.40			33	.18						.36
296.7	298.9	75657	2.2	.0	2F4	4.55	.34	7.51	5.35	143.10			35	.11						.24
298.9	300.7	75658	1.8	.0	2E0	4.62	.33	1.68	1.50	50.40			41	.01						.39
300.7	301.9	75659	1.2	.0	2F4	4.48	.32	7.35	9.35	121.00			32	.03						1.19
301.9	304.1	75660	2.2	.0	2E4	4.44	.30	3.50	1.95	94.20			38	.01						.51
304.1	307.6	75661	3.5	.0	2F0	4.50	.16	4.96	2.08	76.80			36	.04						.24
307.6	310.4	75662	2.8	.0	2E4	4.42	.32	4.30	2.28	64.10			35	.03						.03
310.4	313.2	75663	2.8	.0	2E4	4.23	.06	3.26	1.63	87.40			32	.03						.06
313.2	315.9	75664	2.7	.0	2E0	3.69	.15	1.56	1.64	87.40			26	.07						.04
315.9	318.2	75665	2.3	.0	1D0	3.08	.08	.75	.75	63.00			13	.21						.06
318.2	320.6	75666	2.4	.0	2E4	4.07	.28	1.68	2.81	69.00			32	.03						.20
320.6	323.0	75667	2.4	.0	2E4	4.23	.30	2.01	2.12	66.90			35	.01						.20
323.0	326.1	75668	3.1	.0	2E0	3.86	.28	.62	.63	28.30			31	.13						.17
326.1	329.2	75669	3.1	.0	2E0	3.72	.24	.76	1.56	34.20			26	.09						.16
329.2	332.0	75670	2.8	.0	2E4	3.49	.18	1.16	3.30	32.00			21	.09						.18
332.0	334.8	75671	2.8	.0	2E4	3.57	.15	1.46	3.25	33.00			22	.10						.11
334.8	337.5	75672	2.7	.0	2E4	3.99	.12	2.42	5.57	28.60			30	.07						.11

Waste
include
waste

32

50

40

40

50

50

40

DDH: 81-18

---DEPTHS---				---ASSAYS---																
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
226.0	229.6	75687	3.6	0	2C0	3.31	.17	.07	.14	.90	.34	2	18	21	.03		.02			
229.6	230.8	75688	1.2	0	2E0	2.94	.22	.01	.09	.60	.07	3	30	33	.02		.04			
230.8	234.0	75689	3.2	0	2C0	3.22	.09	.03	.07	5.60	.17	2	16	19	.07		.03			
234.0	237.2	75690	3.2	0	2C0	3.63	.09	.09	.42	.30	.07	3	24	28	.06		.05			
237.2	241.0	75691	3.8	0	2A4F	3.24	.09	.84	10.06	8.70	.07	2	11	14	.09		.04			
241.0	246.0	75692	5.0	0	2A4F	3.33	.08	1.87	5.70	8.70	.48	2	15	17	.06		.02			
246.0	251.0	75693	5.0	0	2A4F	3.35	.12	1.59	3.70	13.10	.69	2	16	18	.10		.02			
251.0	252.8	75694	1.8	0	2F4	4.26	.15	5.65	7.57	79.30	.41	6	16	22	13.86		.28			
252.8	255.0	75695	2.2	0	2F4	4.57	.20	6.54	5.63	107.60	.82	6	22	29	9.92		.45			
255.0	258.6	75696	3.6	0	2F4	4.60	.13	6.43	5.85	102.00	.69	6	23	29	10.14		.51			
258.6	259.0	75697	.4	0	2H0	4.25	.45	1.31	6.11	112.60	.96	12	20	32	2.16		.73			
286.5	288.5	75699	2.0	0	2D0	3.29	.18	3.84	4.19	74.30	.27	6	8	15	5.17		.25			
288.5	293.0	75700	4.5	0	2H4	4.21	.33	4.49	7.08	78.10	.17	15	20	35	.37		.25			
293.0	297.0	75701	4.0	0	2E0	4.70	.16	1.19	1.87	17.40	.07	4	37	42	.07		.07			
297.0	300.0	75702	3.0	0	2E0	4.82	.03	2.80	3.81	33.60	.07	1	38	39	2.27		.02			
300.0	304.2	75703	4.2	0	2E0	4.73	.09	1.32	1.48	19.90	.07	3	40	43	.05		.05			
304.2	308.4	75704	4.2	0	2EF	4.73	.13	3.10	4.98	36.40	.07	3	37	40	.06		.06			
308.4	309.9	75705	1.5	0	2F4	4.82	.08	4.68	7.34	42.30	.07	1	35	37	.12		.04			
309.9	311.7	75706	1.8	0	2E4	4.83	.15	2.41	3.57	22.70	.07		40	41	.17		.01			
311.7	314.0	75707	2.3	0	2F0	4.87	.12	4.24	5.00	43.20	.07	1	38	39	.25		.02			
314.0	318.5	75708	4.5	0	2H4	4.25	.41	2.98	5.05	38.60	.07	19	21	40	.09		.14			
318.5	321.3	75709	2.8	0	2EF4	4.61	.26	5.21	8.20	64.10	.07	5	30	36	.45		.11			
321.3	323.4	75710	2.1	0	2E8	4.50	.39	.89	1.69	17.70	.07	7	34	42	.10		.18			
323.9	326.9	75712	3.0	0	2E8	4.56	.45	1.08	2.68	20.20	.07	5	36	41	.06		.12			
326.9	329.0	75713	2.1	0	2E84	4.55	.24	.93	3.75	14.30	.07	6	34	41	.05		.16			
329.0	331.4	75714	2.4	0	2H4	4.27	.57	3.99	5.64	41.10	.07	20	9	30	.09		.08			
331.4	335.0	75715	3.6	0	2J7	3.86	.58	2.57	5.14	28.00	.07	13	26	40	.06		.10			
335.0	339.0	75716	4.0	0	2D0	3.26	.16	1.40	4.23	24.30	.07	6	6	12	.20		.06			
339.0	343.0	75717	4.0	0	2C0	2.94	.15	1.14	2.85	25.50	.07	6	2	8	.57		.07			
343.0	348.0	75718	5.0	0	2D0	2.71	.03	1.34	2.93	26.10	.07	1	1	3	.24		.03			
348.0	351.0	75719	3.0	0	2D0	2.82	.04	4.00	2.22	74.30	.17	1	1	3	.22		.04			
351.0	354.3	75720	3.3	0	2C0	2.74	.05	.95	2.13	24.30	.41	1	1	3	.24		.03			
354.3	359.0	75721	4.7	0	2D0	2.62	.04	1.21	2.79	28.90	.27	1	1	3	.22		.03			
359.0	364.0	75722	5.0	0	2A4	2.63	.03	1.36	2.84	22.70	.17	1	1	2	.26		.02			
364.0	369.5	75723	5.5	0	2A0	2.70	.04	.88	1.90	16.80	.14	2	1	3	.40		.03			
369.5	372.2	75724	2.7	0	2A0	2.67	.04	.88	1.73	15.20	.17	2	2	4	.36		.04			
372.2	377.0	75725	4.8	0	2A0	2.72	3.11	1.09	1.63	24.90	.17	2	2	5	.25		.04			
377.0	381.0	75726	4.0	0	2A0	2.82	.18	.85	.65	46.00	.27	3	4	8	.18		.04			
381.0	384.0	75727	3.0	0	2A0	2.97	.26	.42	.39	30.20	.07	4	6	10	.11		.04			
384.0	388.0	75728	4.0	0	2A4	2.96	.08	1.73	4.36	28.60	.07	2	5	7	.31		.03			
388.0	393.7	75729	5.7	0	2A4	2.94	.08	2.26	2.61	25.80	.48	1	5	7	.26		.03			
393.7	398.7	75730	5.0	0	2A0	2.73	.04	1.10	2.82	20.20	.07	1	2	3	.43		.03			
398.7	402.0	75731	3.3	0	2A0	2.84	.03	1.14	3.53	20.50	.62	1	3	4	.17		.03			
402.0	406.0	75732	4.0	0	2A4	2.71	.04	1.68	3.08	19.30	.17	1	2	3	.19		.03			
406.0	408.9	75733	2.9	0	2D0	2.86	.06	1.25	3.87	21.50	.96	2	3	5	.23		.03			
408.9	414.0	75734	5.1	0	2A4	2.66	.03	1.36	3.40	17.70	.48	1	1	2	.16		.02			
414.0	419.0	75735	5.0	0	2A4	2.73	.02	1.51	3.19	18.00	.27				.18		.01			
419.0	424.0	75736	5.0	0	2A4	2.72	.02	1.73	3.92	27.40	.75	1		1	.16		.02			
424.0	428.0	75737	4.0	0	2A4	2.72	.04	1.35	3.21	26.40	.96	1	1	3	.23		.03			
428.0	430.0	75738	2.0	0	2D0	2.85	.08	1.38	4.92	30.20	.55	2	1	4	.19		.04			

waste →

33

23

60

70

50

70

21

21

21

21

21

DDH: 81-19

				-----ASSAYS-----																	
DEPTH FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %	S.G. W.R.	
396.0	398.7	75744	2.7	.0	2D0	4.15	.18	3.91	5.58	41.10	.17	5	27	33	.18		.08				
398.7	401.4	75745	2.7	.0	2D4	4.14	.18	1.97	19.51	24.60	.07	7	29	37	.04		.28				
401.4	403.7	75746	2.3	.0	2E82	4.42	.13	.92	2.48	17.10	.07	8	32	41	.04		.54				
403.7	406.0	75747	2.3	.0	2E84	4.58	.08	2.33	3.55	21.80	.07	6	34	41	.04		.35				
406.0	412.0	75748	6.0	.0	2F84	4.50	.33	5.15	7.04	62.50	.07	6	29	36	.03		.44				
412.0	414.4	75749	2.4	.0	2D0	4.11	.19	3.36	3.54	60.30	.82	1	30	32	.03		.05				
414.4	416.9	75750	2.5	.0	2C0	3.64	.80	2.41	.51	89.90	1.37	1	24	25	.03		.02				
416.9	419.7	75751	2.8	.0	2FE4	4.65	.20	5.64	5.07	74.60	.41	2	34	37	.03		.04				
419.7	422.1	75752	2.4	.0	2D0	3.98	.11	3.86	6.14	36.70	.27	1	26	27	.03		.02				
422.1	424.5	75753	2.4	.0	2D0	4.13	.34	2.74	4.76	37.60	.51	1	31	32	.05		.02				
424.5	426.9	75754	2.4	.0	2D0	4.19	.13	2.27	5.94	28.00	.69	1	30	31	.03		.02				
426.9	429.3	75755	2.4	.0	2D0	4.00	.10	3.55	2.82	44.50	1.20	1	28	29	.05		.01				
429.3	431.7	75756	2.4	.0	2D0	4.24	.06	2.58	5.20	33.00	.69	1	31	33	.06		.01				
431.7	434.1	75757	2.4	.0	2D0	4.11	.07	2.49	4.27	26.70	.34	1	30	31	.05		.01				
434.1	436.6	75758	2.5	.0	2C0	3.67	.19	.47	1.39	12.40	.48		26	27	.06		.01				
436.6	439.1	75759	2.5	.0	2D0	3.81	.09	2.48	3.56	24.90	.27		26	27	.06		.01				
439.1	441.8	75760	2.7	.0	2DE4	4.18	.09	6.42	10.12	67.80	.69	2	25	27	.03		.08				
441.8	444.5	75761	2.7	.0	2DE4	4.44	.02	7.68	12.10	63.80	.17	2	26	29	.03		.09				
444.5	447.0	75762	2.5	.0	2D0	3.63	.20	1.91	2.64	20.80	.34	2	22	25	.04		.15				
447.0	449.4	75763	2.4	.0	2C0	3.61	.17	1.26	2.19	23.00	.51	3	22	26	.06		.12				
449.4	451.5	75764	2.1	.0	2D0	3.53	.40	2.65	2.81	34.20	.69	4	19	23	.05		.13				
451.5	453.3	75765	1.8	.0	2E1	4.43	.06	.27	.52	4.70	.86	2	38	40	.05		.03				
453.3	456.0	75766	2.7	.0	2C0	3.89	.08	1.29	1.84	16.80	.55	1	28	30	.05		.03				
456.0	458.7	75767	2.7	.0	2C0	3.92	.10	.25	1.11	3.10	.07	1	30	32	.03		.02				
458.7	461.4	75768	2.7	.0	2D4	4.41	.15	7.60	4.38	44.50	.07	2	30	32	.03		.07				
461.4	464.2	75769	2.8	.0	2D0	4.08	.26	3.42	1.39	28.30	.07	1	31	33	.01		.06				
464.2	465.2	75770	1.0	.0	2D4	3.95	.41	6.43	5.42	46.70	.07	10	17	28	.02		.58				
465.2	467.8	75771	2.6	.0	2D0	4.07	.18	3.85	3.50	29.20	.07	2	29	31	.02		.13				
467.8	470.4	75772	2.6	.0	2C0	4.12	.31	1.70	1.25	14.30	.07	1	32	33	.02		.06				
470.4	473.0	75773	2.6	.0	2C0	4.02	.24	.09	.55	7.50	.07	1	32	33	.01		.03				
473.0	475.6	75774	2.6	.0	2C0	4.41	.21	.07	.42	5.90	.07	1	39	40	.01		.04				
475.6	478.3	75775	2.7	.0	2C0	4.21	.20	.05	.40	2.80	.07	2	34	36	.02		.09				
478.3	481.0	75776	2.7	.0	2D0	4.13	.27	2.02	2.00	18.70	.07	2	32	34	.01		.08				
481.0	484.0	75777	3.0	.0	2D2	4.00	.23	2.31	2.85	21.80	.07	4	27	32	.02		.15				
484.8	486.3	75779	1.5	.0	2E8	4.41	.47	1.97	2.13	21.80	.07	6	33	39	.02		.27				
486.3	487.5	75780	1.2	.0	2F4	4.41	.19	10.24	9.42	67.50	.07	6	23	29	.03		.43				
487.5	490.2	75781	2.7	.0	2D8	4.17	.22	1.07	3.15	9.00	.07	5	29	35	.01		.24				
490.2	492.8	75782	2.6	.0	2C8	4.03	.28	1.18	1.98	12.80	.07	5	27	33	.02		.22				
492.8	495.4	75783	2.6	.0	2C8	4.07	.22	.13	.72	5.30	.07	5	30	36	.03		.20				
495.4	498.0	75784	2.6	.0	2C8	4.01	.33	.78	1.22	15.90	.07	4	29	34	.03		.18				
498.0	500.7	75785	2.7	.0	2D0	3.85	.22	2.25	3.60	14.00	.07	4	24	28	.01		.32				
500.7	503.4	75786	2.7	.0	2D0	3.69	.12	2.24	5.54	14.60	.07	2	22	24	.10		.04				
503.4	506.1	75787	2.7	.0	2C0	3.51	.18	.50	3.10	18.40	.07	2	21	23	.05		.13				
506.1	508.8	75788	2.7	.0	2C0	3.81	.25	.37	.75	8.70	.07	2	28	30	.02		.13				
508.8	511.5	75789	2.7	.0	2C0	3.74	.19	.03	.76	7.50	.07	1	27	29	.03		.09				
511.5	513.6	75790	2.1	.0	2C3	3.66	.20	.08	.32	2.80	.07	1	27	28	.05		.02				
513.6	515.8	75791	2.2	.0	2C3	3.71	.38	.15	.66	10.90	.07	1	26	28	.04		.06				
515.8	518.0	75792	2.2	.0	2C3	3.20	.51	.94	1.96	12.40	.07	1	33	35	.02		.05				
518.0	520.2	75793	2.2	.0	2C3	4.24	.29	.16	1.29	2.20	.07	1	34	36	.01		.04				
520.2	522.3	75794	2.1	.0	2C3	3.92	.36	.66	1.01	10.90	.07	1	30	32	.02		.05				
522.3	524.5	75795	2.2	.0	2C3	4.13	.48	.35	.84	8.70	.07	1	34	35	.04		.01				

DDH: 81-19

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													S.G. W.R.
FROM	TO						CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	
524.5	526.6	75796	2.1	.0	2C3	4.05	40.24	.23	.10	9.30			.07		33	34	.04		.01	
526.6	528.7	75797	2.1	.0	2C3	4.06	.18	1.22	.93	9.00			.07	2	31	34	.02		.06	
528.7	530.8	75798	2.1	.0	2C3	4.25	.16	.47	1.18	4.00			.07	2	34	37	.02		.06	
530.8	533.1	75799	2.3	.0	2F4	3.74	.09	3.19	8.13	10.30			.07	2	22	24	.07		.03	
533.1	535.4	75800	2.3	.0	2F4	3.82	.08	5.00	10.20	12.10			.17	2	21	23	.04		.03	
535.4	537.5	75801	2.1	.0	2D0	3.58	50.05	2.04	5.55	15.90			.07	1	20	22	.11		.03	
537.5	540.7	75802	3.2	.0	2D4	3.51	.12	4.98	12.80	33.90			.07	4	11	16	.10		.05	
540.7	543.8	75803	3.1	.0	2D0	3.12	.09	1.78	2.55	15.90			.07	5	9	14	.16		.04	
543.8	546.9	75804	3.1	.0	2L4	2.93	.10	1.23	4.01	19.00			.34	4	4	8	.24		.05	
546.9	550.0	75805	3.1	.0	2L4	2.97	.11	1.72	4.42	24.30			.55	3	3	7	.34		.05	
550.0	553.1	75806	3.1	.0	2L3	2.82	.07	1.44	1.50	22.70			.27	1	2	3	2.03		.01	
553.1	556.2	75807	3.1	.0	2L3	2.76	.05	1.22	1.81	19.00			.27	1	1	2	.46		.01	
556.2	559.2	75808	3.0	.0	2L3	2.78	.04	1.51	2.53	16.50			.41	1	1	2	.47		.01	
559.2	562.2	75809	3.0	.0	2L3	2.74	.04	1.05	2.20	23.60			.69		1	2	.47		.01	
562.2	565.9	75810	3.7	.0	2A0	2.73	.07	1.29	2.49	19.90			.55	1	1	3	.40		.01	
565.9	568.9	75811	3.0	.0	2L4	2.90	.14	1.08	3.47	20.20			.27	2	4	7	.31		.03	
568.9	571.9	75812	3.0	.0	2L1	2.76	.05	1.05	2.74	14.90			.07	1	1	2	.50		.02	
571.9	574.8	75813	2.9	.0	2L1	2.80	.04	.46	.66	8.70			.07	2	2	5	.38		.09	
574.8	577.7	75814	2.9	.0	2L1	2.78	.11	.55	1.38	11.20			.07	2	2	4	.40		.02	

DDH: 81-20

						-----ASSAYS-----															
DEPTHS	SAMPLE	INT.	REC.	ROCK	S.G.	CU	Pb	Zn	Ag(AA)	Ag(FA)	Au(FA)	Po	Py	TOT	BAO	Hg	Mn	As	Ba	S.G.	
FROM	TO	NO.		UNIT	PULP	%	%	%	g/mT	g/mT	g/mT	%	%	Fe	%	%	%	%	%	W.R.	
221.8	224.5	75820	2.7	.0	2H34	3.79	.38	4.53	5.19	73.10		.07	12	16	28	2.27					.16
224.5	227.3	75821	2.8	.0	2H34	4.36	.29	5.12	8.90	59.70		.07	31	9	41	.07					.13
227.3	229.8	75822	2.5	.0	2E74	4.28	70.24	5.32	8.47	61.30		.07	16	19	36	.02					.13
229.8	232.4	75823	2.6	.0	2E74	4.30	.35	4.76	8.19	61.60		.07	14	21	36	.02					.15
232.4	236.7	75824	4.3	.0	2H34	4.29	.28	5.04	8.93	65.90		.07	30	9	40						.12
236.7	239.9	75825	3.2	.0	2F4	4.38	.05	5.10	7.75	53.50		.07	2	30	33	.01					.05
239.9	246.3	75826	6.4	.0	2F4	4.66	.03	6.96	13.70	58.80		.07	2	29	31	.02					.02
246.3	249.5	75827	3.2	.0	2F4	4.69	.03	8.24	12.60	67.50		.07	1	30	32	.01					.02
249.5	252.7	75828	3.2	.0	2F4	4.74	50.06	3.59	8.06	28.60		.07	1	36	37	.01					.02
252.7	255.9	75829	3.2	.0	2F4	4.54	.11	3.31	6.78	31.70		.07	3	32	36	.01					.10
255.9	257.3	75830	1.4	.0	2F4	4.26	.34	4.82	8.94	50.40		.07	29	9	38	.01					.27
257.3	260.5	75831	3.2	.0	2F4	4.67	.23	6.23	12.20	50.40		.07	3	29	33	.01					.08
260.5	263.6	75832	3.1	.0	2F4	4.64	50.10	4.10	7.87	41.10		.07	3	33	36	.01					.07
263.6	264.6	75833	1.0	.0	2H4	4.30	.40	3.92	7.06	39.20		.07	30	11	41	.21					.10
264.6	267.6	75834	3.0	.0	2FF	4.60	.11	1.98	5.66	21.80		.07	3	34	38	.01					.08
267.6	270.2	75835	2.6	.0	2D5	3.20	.40	.54	4.82	11.80		.07	5	11	16	.23					.07
270.2	272.8	75836	2.6	.0	2D5	3.07	.18	2.18	6.88	27.70		.07	4	6	10	.31					.05
272.8	275.4	75837	2.6	.0	2D5/4	2.98	.08	2.79	8.26	34.20		.34	3	4	7	.22					.03
275.4	277.9	75838	2.5	.0	2D5	2.99	21.07	2.24	4.78	30.50		.27	3	5	9	.21					.03
277.9	281.4	75839	3.5	.0	2A14	3.00	.10	1.73	4.72	28.00		.27	4	6	10	.16					.02
281.4	284.9	75840	3.5	.0	2A14	2.92	.07	.97	3.74	18.00		.07	3	5	8	.16					.02
284.9	288.4	75841	3.5	.0	2A14	2.92	.05	3.39	6.63	39.80		.14	2	3	6	.15					.02
288.4	291.9	75842	3.5	.0	2A14	2.97	.07	1.47	4.78	29.60		.27	3	6	10	.15					.03
291.9	295.2	75843	3.3	.0	2A4	2.86	.06	1.75	4.50	28.00		.07	4	3	7	.21					.06
295.2	298.5	75844	3.3	.0	2A4	2.77	.05	1.69	4.67	29.60		.27	2	2	4	.17					.03
298.5	301.8	75845	3.3	.0	2A4	2.77	21.03	1.70	3.33	21.50		.34	1	2	4	.15					.03
301.8	305.2	75846	3.4	.0	2A4	2.83	.07	1.19	2.53	25.80		.27	2	5	7	.14					.03
305.2	308.6	75847	3.4	.0	2A4	2.87	.05	1.27	3.46	21.50		.27	4	2	7	.29					.05
308.6	312.0	75848	3.4	.0	2A4	2.74	.04	1.54	3.83	23.00		.41	2	2	4	.18					.03
312.0	314.4	75849	2.4	.0	2A0	2.76	.05	1.28	1.38	25.80		.07	3	2	5	.28					.04
314.4	316.7	75850	2.3	.0	2A0	2.74	.05	1.16	1.24	21.20		.17	3	2	5	2.02					.05
316.7	319.0	75851	2.3	.0	2A4	2.74	21.04	2.20	2.06	31.10		.48	2	2	5	.24					.03
319.0	324.9	75852	5.9	.0	2A0	2.59	21.02	.70	1.02	9.60		.07	1		2	2.36					.02
324.9	327.2	75853	2.3	.0	2A0	2.65	.02	.92	2.47	12.40		.07	1		2	.29					.07
327.2	328.5	75854	1.3	.0	2A0	2.69	.03	1.14	2.83	21.20		.07	2	1	3	2.02					.02
335.0	336.0	75856	1.0	.0	2A0	2.86	.12	.32	.58	12.10		.07	3	6	9	.10					.02

DDH: 81017

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														S.G. W.R.
FROM	TO						CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %	
210.0	212.9	75677	2.9	.0	****	2.72	.02	.40	.51	.80			.07	1	2	4	3.27		.05		
226.4	227.6	75679	1.2	.0	****	3.08	.10	1.14	2.53	18.70			.07	5	10	15	2.69		.06		
227.6	229.6	75680	2.0	.0	****	4.32	.22	4.61	7.98	52.90			.07	14	25	40	.07		.10		
229.6	232.6	75681	3.0	.0	****	3.14	.03	.72	3.07	12.10			.07	1	15	16	.04		.02		
232.6	238.8	75682	6.2	.0	****	4.63	.03	5.84	9.85	46.30			.07	1	36	38	.01		.04		
238.8	245.0	75683	6.2	.0	****	4.73	.11	5.31	9.26	37.90			.07	1	38	40	.01		.03		
245.0	248.0	75684	3.0	.0	****	4.73	.03	5.97	9.69	42.30			.07	1	33	35	.01		.02		

DDH: 82F-01

---DEPTHS---		SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													
FROM	TO					CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %
532.5	537.6	82001	5.1	5.1	2C07	3.57	.26	.54	2.07	11.82		.10	5	19	25	.13		.08	
537.6	542.7	82002	5.1	5.1	2C07	3.33	.18	.12	1.81	8.09		.04	8	12	21	.02		.03	
542.7	547.8	82003	5.1	5.1	2C07	3.57	21.19	.23	1.81	8.09		.10	8	16	25	.01		.06	
547.8	552.9	82004	5.1	5.1	2C07	3.57	.14	.32	1.29	7.78		.07	6	17	23	.06		.03	
552.9	556.7	82005	3.8	3.8	2D4	3.45	.05	4.08	12.40	19.91		.10	3	11	15	.10		.02	
556.7	560.7	82006	4.0	4.0	2CE4	4.22	.06	2.48	6.14	19.28		.04	4	24	28	.06		.04	
560.7	564.6	82007	3.9	3.7	2CE4	4.00	21.08	3.65	10.34	30.79		.07	4	21	26	.06		.04	
564.6	567.7	82008	3.1	3.1	2L34	3.05	.13	2.15	3.72	30.79		.10	4	5	9	.20		.03	
567.7	570.8	82009	3.1	3.0	2L3	2.81	.07	.24	.22	9.02		.04	2	3	5	.14		.02	
570.8	575.0	82010	4.2	4.2	2B45	2.94	.11	1.18	4.29	21.77		.07	4	3	7	.19		.02	
575.0	579.2	82011	4.2	4.2	2B45	2.95	21.10	1.93	4.93	51.01		.07	4	3	7	.19		.02	
579.2	583.2	82012	4.0	4.0	2A0	2.88	.16	.67	2.35	16.17		.14	4	4	8	.17		.01	
583.2	587.2	82013	4.0	4.0	2A0	2.78	.14	.52	1.06	10.58		.04	3	3	7	.11		.01	
587.2	591.2	82014	4.0	3.9	2A0	1.79	.08	.65	.91	11.82		.04	2	2	5	.11		.01	
591.2	595.3	82015	4.1	3.7	2A4	2.92	21.13	1.86	2.90	64.07		.07	2	1	4	.24		.03	
600.8	604.8	82016	4.0	4.0	2B05	2.83	.05	.91	1.67	18.97		.07	2	1	4	.24		.03	
604.8	608.9	82017	4.1	4.1	2L14	2.79	.11	.70	1.19	19.91		.04	2	2	5	.13		.01	

DDH: 82F-03

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	---ASSAYS---				Hg %	Mn %	As %	Ba %	S.G. W.R.
FROM	TO												Po %	Py %	TOT Fe	BAO %					
394.8	398.3	82018	3.5	3.5	2GE4	4.43 ⁶⁰	.10	5.37	9.25	101.40		.10	3	19	22	9.96		.12			
423.4	428.3	82019	4.9	4.9	2H46	3.82	.20	2.32	2.40	51.32		.07	10	15	26	4.83		.14			
428.3	432.0	82020	3.7	3.7	2E48	4.72	.24	2.31	2.60	34.52		.10	8	28	36	.15		.29			
432.0	436.3	82021	4.3	4.1	2E8	4.67 ⁴⁰	.36	1.49	1.38	29.86		.04	5	30	36	.03		.17			
436.3	441.0	82022	4.7	4.7	2E0	4.53	.09	.88	.60	16.79			1	32	34	.08		.02			
441.0	449.7	82023	8.7	8.4	2E0	4.51	.08	.77	.42	12.75			1	33	34	.07		.02			
449.7	456.9	82024	7.2	7.2	2C3	3.73	.13	.35	.33	16.49				23	24	.03		.01			
456.9	464.5	82025	7.6	7.6	2C3	3.86 ⁴⁰	.05	.84	.50	18.35				25	26	.02		.01			
464.5	465.3	82026	.8	.8	2H19	3.75	.59	1.06	.23	15.55			30	8	38			.03			
465.3	470.5	82027	5.2	5.2	2CE0	3.92	.09	1.36	1.84	21.46		.14	2	24	26	.01		.02			
470.5	475.7	82028	5.2	5.2	2CE0	3.94	.05	1.15	1.00	29.55		.69		26	26	.01		.01			
475.7	480.8	82029	5.1	5.1	2CE0	3.32 ⁴⁰	.17	2.69	1.01	140.59	5.08		14	15		.01		.01			
480.8	485.9	82030	5.1	5.1	2CE0	3.92	.12	1.66	1.99	22.08		.07	1	24	26	.03		.04			
485.9	491.0	82031	5.1	5.1	2CE4	4.13	.08	2.55	4.65	22.08		.04	2	25	27	.05		.04			
491.0	497.2	82032	6.2	6.2	2A14	3.41 ⁵⁰	.03	2.35	4.68	30.17		.10	1	13	14	.24		.01			
497.2	501.8	82033	4.6	4.6	2CE4	4.26	.20	1.64	2.92	18.35		.04	5	25	31	.01		.17			
501.8	506.4	82034	4.6	4.6	2CE4	4.00 ⁴⁰	.37	1.74	2.83	18.97		.04	5	22	27	.01		.20			
506.4	511.0	82035	4.6	4.6	2CE8	3.91	.56	1.12	1.60	20.84		.04	5	21	26	.01		.14			
511.0	515.2	82036	4.2	4.2	2F10	4.55	.17	3.58	5.93	28.30		.04	7	24	31	.02		.29			
515.2	519.3	82037	4.1	4.1	2F14	4.19	.21	5.30	7.08	34.53		.04	5	20	26			.15			
519.3	523.4	82038	4.1	4.1	2F14	4.53 ⁵⁰	.20	6.30	10.03	40.44		.04	7	20	28	.01		.31			
523.4	528.6	82039	5.2	5.2	2CE0	4.33	.21	1.38	2.54	9.64		.04	6	25	32	.01		.18			
528.6	533.7	82040	5.1	5.1	2CE0	3.89	.33	.40	1.10	8.71		.14	4	23	27	.02		.11			
533.7	538.8	82041	5.1	5.1	2CE0	3.94 ⁴⁰	.39	.39	1.69	7.15		.04	4	23	27	.07		.10			
538.8	543.1	82042	4.3	4.3	2D34	4.15	.15	3.40	8.47	12.75		.04	3	21	25	.01		.05			
543.1	547.3	82043	4.2	4.2	2D34	4.48	.09	4.67	8.83	15.24		.04	2	25	27	.03		.02			
547.3	551.5	82044	4.2	4.2	2D34	4.24 ²¹	.07	6.02	10.64	19.28		.04	3	21	24	.02		.02			
551.5	554.8	82045	3.3	3.3	2D34	4.15	.08	1.51	4.34	7.15		.04	2	24	27	.01		.03			
554.8	558.2	82046	3.4	3.4	2D34	4.07	.06	5.22	10.09	24.88		.04	2	18	21	.05		.03			
558.2	562.7	82047	4.5	4.5	2B05	2.87	.11	.82	1.44	22.08		.34	2	1	4	.31		.03			
562.7	567.2	82048	4.5	4.5	2B05	2.92	.12	1.79	1.57	26.44		.14	2	2	4	.24		.02			
567.2	571.7	82049	4.5	4.5	2B05	2.94 ²¹	.15	.41	1.49	12.13		.14	3	3	7	.18		.01			
571.7	576.2	82050	4.5	4.5	2B05	2.92	.22	.44	1.37	19.60		.28	3	3	6	.17		.02			
576.2	580.5	82051	4.3	4.3	2D4	3.41	.29	3.23	10.10	39.19		.21	4	8	13	.09		.03			

note

DDH: 82F-05

---DEPTHS---			SAMPLE INT. NO.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													S.G. W.R.
FROM	TO	CU %					Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %	
273.2	277.7	82052	4.5	4.5	2A4	3.25	30	.62	3.83	14.61			.10	5	10	15	.04			.03
277.7	282.2	82053	4.5	4.5	2A4	2.89	23	06	5.18	9.88	30.17			.28	2	9	11	.05		.01
282.2	287.2	82054	5.0	4.8	2E24	4.82	50	08	3.14	3.52	36.08			.07	2	26	28	.02		.04
287.2	291.4	82055	4.2	4.2	2E74	4.45	50	20	6.32	8.47	130.33			.14	9	16	25	1.12		.24
291.4	296.8	82056	5.4	5.4	2B4	3.12	32	15	3.37	7.55	49.46			.07	4	4	8	.22		.15
296.8	302.2	82057	5.4	4.7	2B4	2.86	32	06	2.47	3.87	30.01			.07	2	2	5	.07		.05
302.2	306.6	82058	4.4	4.4	2E4	4.45		.32	6.42	7.38	113.53			.17	12	14	26	.09		.32
306.6	310.2	82059	3.6	3.6	2H4	4.40	70	42	4.39	6.93	69.36			.07	38		39	.54		.14
310.2	313.7	82060	3.5	3.0	2H4	4.39	70	41	2.92	3.39	51.32			.10	40	2	42	.05		.06
313.7	318.7	82061	5.0	4.9	2H4	4.40		.52	2.62	3.87	48.83			.10	43		43	.03		.05
318.7	323.7	82062	5.0	5.0	2H4	4.44		.50	2.87	4.31	53.81			.10	43		44	.03		.06
323.7	328.7	82063	5.0	5.0	2H4	4.23	70	55	2.64	2.76	60.03			.14	40		40	.02		.06
328.7	333.9	82064	5.2	5.2	2H4	4.41		.42	3.38	5.35	61.51			.14	42		42	.01		.08
333.9	338.8	82065	4.9	4.9	2B57	3.03		.26	.52	1.76	21.77			.10	10	1	12	.25		.01
338.8	344.0	82066	5.2	5.2	2B5	2.87		.13	.72	1.55	14.00			.07	5	2	8	.29		.01
344.0	349.0	82067	5.0	5.0	2A0	2.69	21	.04	.36	.93	12.44			.07	4		4	.43		.05
349.0	354.0	82068	5.0	5.0	2A0	2.69		.02	.59	1.50	6.53			.04	1	1	3	.54		.02
354.0	359.0	82069	5.0	5.0	2A4	2.77	21	.08	1.38	2.94	25.82			.10	2	1	3	.71		.02
359.0	363.9	82070	4.9	4.9	2A0	2.77		.03	.82	1.71	16.49			.17	2	2	4	.44		.01

56.2
3.47, 5.54, 59.4
0.70

DDH: 82F-06

Handwritten notes:
 481.6 to 512.0
 and
 512.0 to 533.0

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----											S.G. W.R.
FROM	TO						CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	
462.2	464.6	82071	2.4	2.2	2DE	3.38	.21	1.38	4.34	16.17		.14	14	7	22	.55		.09
464.6	469.0	82072	4.4	4.4	2G0	4.63	.03	3.15	5.37	32.04		.14	1	16	17	29.87		.01
469.0	473.5	82073	4.5	4.5	2G4	4.59	<i>60</i> .06	4.17	6.33	56.92		.10		10	11	42.93		.01
473.5	476.8	82074	3.3	3.3	2E4	4.51	.03	4.13	6.36	42.30		.10	1	28	29	2.26		.01
476.8	480.0	82075	3.2	3.0	2E4	4.60	.03	4.57	7.68	52.25		.07	1	25	27	2.99		.01
480.0	484.8	82076	4.8	4.8	2G0	3.48	<i>60</i> .04	2.85	5.07	30.48		.10		14	15	37.90		.01
484.8	489.6	82077	4.8	4.8	2G4	4.51	.05	3.56	6.52	57.23		.10	2	16	18	26.42		.06
512.0	515.9	82078	3.9	3.9	2A0	2.73	.02	.39	.38	4.04			2	2	4	2.87		.02
515.9	519.8	82079	3.9	3.9	2A0	2.74	.02	.23	.30	5.91			2	2	4	2.80		.02
519.8	525.9	82080	6.1	6.1	2L0	3.04	<i>Waste</i> .05	.81	1.00	12.75			4	4	8	2.87		.08
525.9	528.9	82081	3.0	3.0	2A0	2.78	.03	.45	.36	6.22			1	2	3	3.38		.03
528.9	533.0	82082	4.1	4.1	2L41	2.92	.06	1.19	1.94	17.42		.10	4	3	7	4.72		.10
533.0	537.1	82083	4.1	4.1	2E4	4.44	.13	4.75	6.40	75.58		.14	8	19	27	6.19		.11
537.1	541.2	82084	4.1	4.1	2E4	4.08	.23	4.63	6.52	71.54		.14	12	17	29	.16		.09
541.2	545.3	82085	4.1	4.1	2E4	4.33	.30	5.72	8.17	100.46		.14	21	11	33	.57		.07
545.3	548.8	82086	3.5	3.5	2D0	2.84	<i>50</i> .06	1.62	2.50	41.99		.10	3	2	6	.12		.03
548.8	552.2	82087	3.4	3.4	2D07	2.87	.14	3.90	2.96	122.55		.17	8	7	15	.47		.07
552.2	555.7	82088	3.5	3.5	2E47	4.38	.15	4.33	5.02	95.49		.21	7	22	30	.38		.14
555.7	559.1	82089	3.4	3.4	2E07	4.15	.28	.63	.44	12.75			16	18	34	.01		.09
559.1	563.4	82090	4.3	4.3	2H0	4.36	.43	.75	.21	18.97			37	6	43	.01		.11
563.4	567.2	82091	3.8	3.8	2E0	4.71	<i>40</i> .15	1.05	.74	21.46			7	28	35	.01		.19
567.2	569.5	82092	2.3	2.3	2E8	4.70	.11	1.09	1.07	25.19		.14	9	27	36	.03		.33
569.5	575.0	82093	5.5	5.5	2E4	4.48	.28	3.32	4.72	59.41		.10	9	24	33	.01		.27
575.0	580.5	82094	5.5	4.0	2E48	4.58	<i>50</i> .20	2.06	2.74	37.95		.07	9	25	34	.01		.37
580.5	589.9	82095	9.4	5.7	2F0	4.48	.16	2.73	3.89	39.50		.07	1	30	32	.01		.01
589.9	604.0	82096	14.1	6.0	2F0	4.76	.06	3.22	6.03	36.08		.04	1	32	33	.02		.02
604.0	608.4	82097	4.4	3.4	2F4	4.70	<i>50</i> .07	4.76	9.66	44.48		.07	2	29	31	.02		.02
608.4	612.8	82098	4.4	3.2	2F4	4.89	.03	4.07	7.88	41.06		.04	1	31	33	.35		.02
612.8	615.5	82099	2.7	2.2	2G0	4.85	.03	2.71	6.83	29.24		.04	1	25	27	11.08		.03
615.5	617.8	82100	2.3	2.0	2E41	4.23	.16	2.90	3.42	31.73		.04	3	26	30	.30		.13
617.8	622.0	82101	4.2	4.1	2F4	4.76	.10	5.43	10.60	65.32		.07	4	25	29	.03		.09
622.0	625.4	82102	3.4	3.4	2H43	4.31	<i>60</i> .54	4.13	8.87	48.21		.04	29	8	37	.03		.17
625.4	629.4	82103	4.0	4.0	2F41	4.63	.17	4.26	9.11	36.08		.04	6	24	30	.04		.16
629.4	633.4	82104	4.0	4.0	2G41	4.53	.19	7.28	7.52	37.64		.07	4	21	26	9.37		.15
633.4	637.4	82105	4.0	4.0	2G0	4.49	<i>60</i> .15	2.61	5.60	31.73		.07	3	23	26	7.03		.09
637.4	641.8	82106	4.4	4.4	2F4	4.46	.17	4.24	9.28	32.04		.07	4	24	28	1.20		.14
641.8	646.3	82107	4.5	4.5	2F4	4.89	.14	4.70	8.90	39.81		.04	2	26	29	3.45		.08
646.3	650.8	82108	4.5	4.5	2F0	4.66	.19	3.27	6.28	34.46		.04	6	26	33	.89		.25
650.8	655.3	82109	4.5	4.5	2F4	4.79	.22	5.69	8.30	51.32		.04	5	24	29	3.94		.21
655.3	660.3	82110	5.0	5.0	2F0	4.57	.17	2.77	6.19	21.46		.07	4	27	31	.06		.09
660.3	665.3	82111	5.0	5.0	2F0	3.99	.26	2.95	5.94	34.21		.07	13	18	31	.04		.09
665.3	670.3	82112	5.0	5.0	2F4	4.66	<i>50</i> .06	3.19	6.71	22.08		.07	3	31	34	.01		.03
670.3	675.3	82113	5.0	5.0	2F4	4.71	.12	4.42	8.35	32.35		.07	5	26	31	.03		.02
675.3	679.2	82114	3.9	3.9	2D3	3.04	.07	2.13	4.15	27.05		.14	4	6	11	.53		.06
679.2	683.1	82115	3.9	3.9	2D3	3.12	.05	1.71	4.74	21.46		.10	4	8	12	.16		.03
683.1	687.0	82116	3.9	3.9	2D34	3.37	<i>21</i> .03	2.11	8.26	33.90		.28	3	13	16	.16		.02
687.0	690.8	82117	3.8	3.8	2D5	3.04	.05	1.57	5.37	24.88		.17	3	3	6	.28		.01
690.8	694.7	82118	3.9	3.9	2D5	2.97	.06	2.19	5.73	30.48		.07	4	5	9	.18		.01
694.7	697.0	82119	2.3	2.3	2A4	3.09	.03	2.75	6.70	35.15		.28	3	3	6	.30		.02
697.0	702.3	82120	5.3	5.3	2D3	3.31	.06	2.69	6.03	35.77		.17	4	11	16	.16		.01
702.3	707.6	82121	5.3	5.3	2D3	3.21	<i>21</i> .20	2.75	4.99	50.70		.28	6	7	13	.21		.03

DDH: 82F-06

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													S.G. W.R.		
FROM	TO						CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %		Ba %	
707.6	712.9	82122	5.3	5.3	2D3	3.22	.09	2.95	5.57	37.64		.10	4	8	12	.17		.01				
712.9	718.3	82123	5.4	5.4	2D43	3.40	.05	3.63	6.84	40.12		.17	4	11	15	.12		.03				
718.3	723.7	82124	5.4	5.4	2D3	3.42	.04	2.01	6.85	27.99		.14	4	11	16	.12		.02				
723.7	729.1	82125	5.4	5.4	2D3	3.26	.06	2.55	5.81	35.46		.21	5	9	14	.16		.01				
729.1	734.5	82126	5.4	5.4	2D43	3.39	.08	3.90	6.90	46.35		.17	6	7	14	.09		.01				
734.5	739.2	82127	4.7	4.7	2C35	3.33	.13	1.31	3.19	17.11		.10	10	8	18	.07		.02				
739.2	743.9	82128	4.7	4.7	2C35	3.50	.08	2.51	4.32	36.08		.14	4	14	19	.06		.01				
743.9	748.6	82129	4.7	4.7	2C35	3.21	.11	1.56	2.90	29.55		.10	8	6	15	.11		.01				
748.6	753.3	82130	4.7	4.7	2C35	3.13	.11	1.19	3.75	28.93		.07	5	7	13	.07		.01				
753.3	756.4	82131	3.1	3.1	2A41	2.89	.06	1.91	4.99	33.28		.62	2	2	5	.11		.01				
756.4	759.4	82132	3.0	3.0	2A41	2.86	.06	1.70	2.86	33.90		.21	4	2	6	.17		.04				

DDH: 82F-08

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	---ASSAYS---										S.G. W.R.
FROM	TO									Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	
361.9	366.1	82145	4.2	4.2	2CE0	3.32	33.24	.08	.07	17.11				1	17	18	.01			.02
366.1	369.6	82146	3.5	3.5	2C3	3.77	60.18	.03	.03	10.89				5	21	26	.02			.05
369.6	373.0	82147	3.4	3.4	2C3	3.62	60.41	.42	.26	15.86				11	14	26	.02			.08
373.0	378.1	82148	5.1	5.1	2E4	4.12	.23	4.57	6.58	76.20				7	18	26	2.55			.31
378.1	383.4	82149	5.3	5.3	2C56	2.77	.02	.68	.57	6.53				2	2	4	4.04			.06
383.4	388.9	82150	5.5	5.5	2L14	3.00	22.02	2.00	2.57	36.08				4	3	7	3.16			.08
388.9	393.9	82151	5.0	4.9	2A0	2.81	22.01	.60	.69	8.40				3	2	5	3.13			.03
393.9	398.9	82152	5.0	4.5	2A0	2.89	.01	.55	.73	8.40				2	1	4	3.01			.04
398.9	402.4	82153	3.5	3.5	2L0	3.08	.06	.95	.64	16.49				4	5	9	2.55			.04
402.4	406.0	82154	3.6	3.4	2L0	3.01	Waste	.48	.67	7.15				2	2	5	3.36			.03
406.0	410.1	82155	4.1	4.0	2L14	3.14	.07	1.83	2.18	31.42			.07	4	4	9	7.92			.09
410.1	414.2	82156	4.1	4.1	2L14	3.16	.06	2.88	2.42	62.52			.07	6	4	11	4.51			.13
414.2	419.7	82157	5.5	5.5	2H4	3.73	.15	6.67	6.10	135.92			.07	21	2	24	.12			.16
419.7	425.2	82158	5.5	5.5	2H4	3.94	70.25	4.39	7.73	90.20			.07	22	7	29	.19			.14
425.2	430.7	82159	5.5	5.4	2H4	4.48	.31	6.86	7.15	148.05			.07	24	8	32	3.61			.24
430.7	436.3	82160	5.6	5.6	2E42	4.80	50.11	2.97	3.82	33.59			.07	7	29	36	.05			.08
436.3	441.9	82161	5.6	5.4	2E42	4.70	.20	2.75	4.16	39.50			.07	12	26	39	.07			.07
441.9	445.6	82162	3.7	3.7	2D5	3.07	21.20	3.05	6.08	72.16			.10	5	6	11	.18			.06
445.6	449.7	82163	4.1	4.1	2D5	3.16	.20	1.07	3.22	29.86			.07	8	3	11	.23			.05
449.7	451.9	82164	2.2	2.2	2H4	4.36	.51	2.78	4.41	40.44			.07	42	2	44	.02			.12
451.9	457.6	82165	5.7	5.7	2E2	4.63	50.65	1.12	1.82	20.53			.10	12	25	38	.03			.17
457.6	463.2	82166	5.6	5.6	2E2	4.18	.27	.83	3.60	10.26			.07	5	27	33	.03			.14
463.2	468.8	82167	5.6	5.6	2E2	4.80	.14	3.00	4.82	18.04			.07	2	31	34	.02			.06
468.8	472.4	82168	3.6	3.6	2D4	3.33	.13	.52	3.50	9.64			.14	3	14	17	.16			.03
472.4	474.2	82169	1.8	1.8	2E0	4.44	50.21	.18	2.21	7.78			.07	3	31	35	.04			.04
474.2	476.4	82170	2.2	2.2	2L0	3.04	.19	.96	.48	14.00			.07	5	9	14	.15			.01
476.4	480.0	82171	3.6	3.6	2E4	4.34	.22	4.97	8.00	99.22			.14	9	22	31	.02			.09
496.0	498.5	82172	2.5	2.4	2A1	2.93	21.11	.13	.31	10.58				4	3	8	.11			.03
498.5	502.0	82173	3.5	3.5	2L0	2.86	.04	.03	.06	6.53				2	1	3	.19			.01
502.0	505.6	82174	3.6	3.6	2C5	2.88	.15	.34	.37	51.01				5	5	10	.15			.03
505.6	509.3	82175	3.7	3.7	2C5	3.08	21.18	.14	.11	13.38				7	7	14	.10			.05
509.3	514.4	82176	5.1	5.1	2A0	2.93	.13	.33	.16	9.64				5	2	8	.18			.01
514.4	519.5	82177	5.1	5.1	2A0	2.97	21.13	1.39	.48	27.99				5	3	9	.16			.01
519.5	524.8	82178	5.3	5.1	2A41	2.75	.03	1.54	3.10	13.69				1		1	.19			.01
524.8	530.0	82179	5.2	4.0	2A1	2.87	.07	1.16	2.40	26.13				2	1	4	.20			.03

Waste

37.7
0.22 1.04, 5.45, 7.13

DDH: 82F-09

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													S.G. W.R.
FROM	TO						CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe %	BAO %	Hg %	Mn %	As %	
491.2	495.8	82180	4.6	4.6	2E4	3.70	.18	2.74	4.79	42.61		.10	6	12	19	2.79		.12		
495.8	500.3	82181	4.5	4.5	2E4	4.41	.12	4.83	4.26	79.00		.17	7	16	23	4.38		.39		
500.3	504.8	82182	4.5	4.5	2E4	4.29	.21	6.63	5.58	107.93		.10	8	12	20	8.48		.45		
504.8	509.5	82183	4.7	4.7	2A0	2.83	.01	.25	.30	5.91			2	1	4	2.45		.07		
509.5	514.3	82184	4.8	4.8	2A0	2.79	.02	.40	.52	6.53			2	2	4	2.52		.06		
514.3	519.1	82185	4.8	4.8	2A0	2.79	.03	.51	.80	7.78			2	2	4	1.35		.06		
519.1	523.9	82186	4.8	4.8	2A0	2.68	.02	.25	.30	.93			2	1	3	2.34		.02		
530.4	533.4	82187	3.0	3.0	2D4	3.47	.13	6.35	7.05	137.79		.07	8	5	14	.73		.21		
536.5	540.6	82188	4.1	4.1	2B0	2.87	.04	.86	1.61	10.26		.04	3	2	5	.26		.05		
540.6	544.7	82189	4.1	4.1	2B0	3.03	.06	1.20	2.35	21.46		.04	3	4	8	.08		.06		
547.7	552.2	82190	4.5	4.0	2B4	3.19	.14	8.38	1.95	144.01		.14	5	5	10	.05		.10		
552.2	556.6	82191	4.4	4.2	2B4	3.27	.10	7.90	3.39	162.67		.10	4	6	11	.07		.10		
556.6	561.5	82192	4.9	4.9	2B4	3.09	.08	3.67	1.96	69.05		.04	4	3	8	.07		.06		
561.5	566.4	82193	4.9	4.9	2B0	3.08	.09	.76	1.72	17.11		.04	7	4	11	.46		.09		
566.4	571.2	82194	4.8	4.8	2C0	3.21	.24	.84	1.95	13.37		.07	8	8	16	.18		.07		
571.2	574.2	82195	3.0	3.0	2E42	4.72	.15	3.30	5.63	35.46		.04	4	28	32	.02		.09		
574.2	577.3	82196	3.1	3.1	2E42	4.81	.13	3.57	6.51	36.39		.04	3	29	33	.02		.06		
577.3	581.7	82197	4.4	4.4	2H4	4.51	.45	2.29	4.15	29.24		.04	24	14	38	.03		.14		
581.7	586.1	82198	4.4	4.4	2H4	4.51	.48	3.79	6.46	31.10		.04	29	8	37	.03		.09		
586.1	590.5	82199	4.4	4.4	2H4	4.51	.62	2.66	5.06	35.15		.04	24	14	38	.02		.16		
590.5	596.0	82200	5.5	5.5	2E2	4.18	.27	1.94	3.58	14.31		.04	7	23	31	.05		.17		
596.0	600.5	82201	4.5	4.5	2A0	3.20	.16	1.06	2.06	22.71		.04	10	4	15	.14		.15		
600.5	604.9	82202	4.4	4.4	2A0	3.14	.11	.94	2.10	22.71		.04	6	7	13	.18		.08		
604.9	609.3	82203	4.4	4.4	2A4	3.08	.10	1.48	2.53	40.12		.04	5	6	12	.16		.05		
609.3	612.6	82204	3.3	3.3	2C0	3.00	.08	.62	2.62	19.91		.04	5	4	10	.21		.05		
612.6	615.9	82205	3.3	3.3	2D0	3.13	.14	3.17	4.87	93.62		.04	5	6	12	.20		.03		
615.9	619.2	82206	3.3	3.3	2A0	2.83	.05	1.11	2.82	25.82		.04	3	1	4	.20		.06		
619.2	624.8	82207	5.6	5.6	2C0	2.99	.08	.19	.22	5.91			3	4	7	.22		.04		
624.8	630.3	82208	5.5	5.5	2L12	2.84	.04	.42	.69	9.02			2	1	4	.27		.04		
630.3	635.8	82209	5.5	5.4	2D0	3.25	.19	3.48	4.14	81.49			7	8	15	.09		.10		
635.8	641.3	82210	5.5	5.5	2L12	2.90	.08	.58	.12	18.35			4	3	8	.22		.06		

Include waste from 5217-528
Include waste from 5217-528
Include waste from 5217-528

13.6
0.17, 0.72, 1.88, 76.26

3.0
0.12, 3.14, 2.67, 53.34

8.9
0.40, 3.08, 5.49, 33.13

19.3

DDH: 82F-10

-----DEPTHS-----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
517.2	519.7	82211	2.5	2.5	0Q9	2.96		.70	2.54	18.97						.19					.08
519.7	521.5	82212	1.8	1.8	2L0	2.84		.12	.09	3.73						.26					.04
521.5	526.0	82213	4.5	4.5	2A0	2.77		.40	.57	9.64						.32					.04
526.0	530.5	82214	4.5	4.3	2A0	2.83		1.33	3.59	23.33						.18					.03
530.5	533.4	82215	2.9	2.9	2E46	4.03		4.82	6.77	79.63						1.41					.04
533.4	536.6	82216	3.2	3.2	2E46	4.26		4.97	9.14	65.32						2.23					.08
536.6	539.8	82217	3.2	3.2	2E4	4.24		5.50	9.77	78.07						.29					.09
539.8	541.9	82218	2.1	2.1	2D06	2.99		4.51	5.41	89.58						1.12					.06
541.9	543.7	82219	1.8	1.8	2H4	4.08		5.85	8.51	110.11						.96					.08
543.7	548.8	82220	5.1	5.1	2A0	2.89		.97	1.75	21.77						.24					.04
548.8	553.9	82221	5.1	5.1	2A0	2.89		.51	1.17	22.39						.20					.01
553.9	556.9	82222	3.0	3.0	2A0	2.80		.70	1.35	23.33						.23					.01
566.4	570.2	82223	3.8	3.8	2A1	2.76		.57	.98	15.86						.23					.04
570.2	574.1	82224	3.9	3.9	2A1	2.87		.88	1.83	16.49						.18					.03

Saste

23

50

21

21

*13.21
0.16, 511, 8.09, 81.52*

DDH: 82F-11

-----DEPTHS-----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
496.6	500.8	82225	4.2	4.2	2A4	3.00	.10	1.39	4.28	13.38			.07	4	7	12	.07				.05
500.8	505.0	82226	4.2	4.2	2A4	3.19	.08	3.11	7.43	25.51			.55	2	5	7	.10				.01
505.0	510.0	82227	5.0	5.0	2E4	4.44	.20	5.70	5.85	79.32			.14	4	21	26	4.25				.15
510.0	515.0	82228	5.0	5.0	2E4	4.74	.11	5.74	6.61	96.11			.14	5	18	23	8.59				.21
515.0	519.5	82229	4.5	4.5	2H4	4.12	.35	4.89	5.87	90.20			.07	16	12	28	4.56				.25
519.5	524.0	82230	4.5	4.5	2H0	4.53	.49	2.96	5.00	46.66			.04	33	5	38	.07				.11
524.0	528.0	82231	4.0	4.0	2D0	3.03	.13	2.70	4.35	50.08			.04	6	5	12	.13				.09
528.0	532.1	82232	4.1	4.1	2D0	2.95	.08	1.24	2.97	25.19			.04	3	3	7	.19				.05
532.1	536.2	82233	4.1	4.1	2D0	3.02	.12	1.93	3.53	33.90			.04	4	4	9	.14				.05
536.2	539.6	82234	3.4	3.4	2A4	2.79	.12	1.20	3.25	24.88			.04	4	2	7	.34				.05
539.6	543.0	82235	3.4	3.4	2A0	2.82	.09	1.17	2.32	23.33			.04	3	2	5	.44				.02
543.0	547.0	82236	4.0	4.0	2B45	2.80	.08	1.20	2.61	21.46			.04	4	3	7	.34				.04
547.0	550.9	82237	3.9	3.9	2B45	3.00	.15	1.52	3.33	47.90			.04	5	3	8	.32				.03
550.9	555.8	82238	4.9	4.4	2A0	2.78	.05	.96	1.76	19.28			.04	2	3	5	.26				.03
555.8	560.7	82239	4.9	4.0	2A0	2.74	.05	1.37	1.50	31.42			.07	2	2	5	.44				.03
560.7	565.6	82240	4.9	4.9	2A0	2.84	.06	1.12	1.39	25.19			.14	2	2	5	.36				.03
565.6	570.5	82241	4.9	4.8	2A0	2.73	.03	1.09	2.48	15.24			.14	2	3	3	.36				.02
570.5	575.5	82242	5.0	3.7	2A4	2.79	.03	1.22	3.27	15.24			.14	2	3	3	.50				.03

31.4
0.21, 3.89, 5.66, 59.13

DDH: 82F-12

-----DEPTHS-----				-----ASSAYS-----																
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
335.2	340.0	82243	4.8	4.6	2E4	3.28	.12	4.22	8.01	52.88	.10	4	9	13	.07		.11			
340.0	344.4	82244	4.4	4.4	2DA0	2.88	.06	3.35	4.38	46.66	.04	2	2	5	.11		.07			
344.4	348.7	82245	4.3	4.3	2DA0	2.96	.05	2.07	2.95	30.79	.04	4	2	6	.40		.05			
348.7	353.0	82246	4.3	4.3	2DA0	2.92	.05	1.91	3.30	26.13	.04	3	2	6	.29		.06			
353.0	357.3	82247	4.3	4.3	2CA0	2.82	.06	.94	2.13	16.80	.04	5	2	7	.55		.07			
357.3	361.9	82248	4.6	4.2	2H0	4.02	.32	2.39	4.42	42.92	.04	26	6	32	.32		.08			
361.9	366.9	82249	5.0	5.0	2D5	2.97	.13	1.54	2.85	29.55	.04	5	4	9	.44		.04			

DDH: 82F-13

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														S.G. W.R.
FROM	TO						CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %	
559.5	565.3	82250	5.8	5.8	2A01	2.83	.08	.66	2.28	17.73			.07	4	2	7	.17		.04		
565.3	571.0	82251	5.7	5.4	2A01	2.78 ²³	.02	.87	2.25	17.73			.04	3	1	4	.32		.03		
571.0	575.6	82252	4.6	4.3	2B4	2.93	.03	1.95	3.62	36.08			.04	4	3	7	.23		.03		
575.6	580.1	82253	4.5	4.3	2B0	2.76 ²³	.02	.97	2.01	19.60			.04	2	1	3	.14		.01		
580.1	584.6	82254	4.5	4.1	2B0	2.79	.04	.66	2.50	17.11			.04	3	1	4	.16		.01		
584.6	588.0	82255	3.4	3.4	2D47	3.40	.21	4.16	8.31	89.89 ^{6.8}			.04	11	4	15	.20		.05		
588.0	591.4	82256	3.4	3.2	2D07	2.96 ⁵⁰	.38	2.18	4.10	49.77			.04	4	5	9	.19		.02		

DDH: 82F-14

---DEPTHS---		SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	---ASSAYS---										S.G. W.R.
FROM	TO											Po %	Py %	TOT Fe %	BAO %	Hg %	Mn %	As %	Ba %			
550.8	555.7	82257	4.9	4.9	2A1	2.98	.12	.32	.65	7.47			3	7	11	.12						.03
555.7	560.6	82258	4.9	4.9	2A0	3.15	23.07	1.28	2.02	12.44			.21	2	9	12	.08					.01
560.6	565.5	82259	4.9	4.9	2A41	2.95	.06	1.27	3.46	14.93			.82	2	7	9	.17					.03
565.5	569.4	82260	3.9	3.9	2F48	4.35	.09	5.40	9.53	61.90			.04	5	21	26	.08					.12
569.4	573.2	82261	3.8	3.8	2F48	4.64	50.11	5.15	6.06	78.38			.10	6	25	31	1.21					.21
573.2	578.1	82262	4.9	4.9	2F46	4.37	.16	4.52	6.50	71.54			.14	7	21	28	3.62					.27
578.1	583.0	82263	4.9	4.9	2F46	4.49	70.18	4.78	5.53	77.76			.17	8	20	29	4.82					.30
583.0	587.6	82264	4.6	4.6	2H42	4.27	70.36	6.46	8.28	104.82			.10	22	10	32	.69					.21
587.6	592.0	82265	4.4	4.4	2E48	4.26	50.21	4.89	7.18	76.83			.07	8	18	27	3.07					.21
592.0	596.3	82266	4.3	4.3	2E48	4.31	50.54	5.57	9.33	74.34			.04	5	19	25	2.06					.11
596.3	600.3	82267	4.0	4.0	2A4	2.95	21.10	1.90	3.08	29.86			.04	5	3	9	.25					.07
608.5	614.0	82268	5.5	5.5	2B5	2.91	.07	.96	2.34	18.35			.04	4	1	6	.18					.03
618.7	624.4	82269	5.7	5.7	2A0	2.90	.05	.65	1.06	14.31			.04	3	2	6	.17					.17
624.4	630.1	82270	5.7	5.3	2A0	2.88	21.07	1.47	1.41	36.08			.04	3	2	6	.30					.41
630.1	635.7	82271	5.6	5.6	2A4	2.94	.09	3.78	3.02	83.05			.14	3	2	5	.26					.06
635.7	641.3	82272	5.6	5.6	2A4	3.03	21.14	1.78	4.30	40.44			.41	7	3	10	.34					.04
641.3	646.9	82273	5.6	5.6	2A0	2.14	.06	1.18	.83	24.88			.04	4	1	5	.57					.18

Ind. white

*30.81
0.24, 5.24, 7.43, 78.27*

DDH: 82F-15

---DEPTHS---		SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	---ASSAYS---					Hg %	Mn %	As %	Ba %	S.G. W.R.
FROM	TO											Po %	Py %	TOT Fe	BAO %						
590.3	595.5	82274	5.2	5.0	2LHA*	3.39	.51	.45	.52	23.02		10	11	21	.11					.03	
595.5	598.4	82275	2.9	2.8	2D0	3.28	23.13	2.39	7.46	26.44		.41	2	11	13	.07				.05	
598.4	601.2	82276	2.8	2.8	2A1	2.28	.09	2.03	5.78	28.93		.07	1	7	8	.16				.01	
601.2	605.2	82277	4.0	3.8	2E4	4.81	.16	4.34	4.86	60.65		.17	5	27	32	.96				.19	
605.2	609.3	82278	4.1	4.1	2E4	3.16	50.11	4.08	5.27	64.99		.10	5	26	31	3.99				.14	
609.3	610.2	82279	.9	.9	2H2	4.22	.54	4.99	6.26	97.04		.17	19	10	29	4.65				.35	
610.2	615.4	82280	5.2	5.2	2A4	2.22	.09	2.18	4.85	31.42		.07	6	1	7	.47				.05	
615.4	620.6	82281	5.2	5.2	2A4	3.00	21.12	1.85	3.62	32.04		.04	4	3	8	.30				.03	
620.6	625.7	82282	5.1	4.7	2A0	2.93	.11	.94	1.78	27.99		.07	4	4	8	.55				.03	
625.7	630.8	82283	5.1	5.1	2A4	2.28	.09	1.46	4.29	31.42		.04	6	3	9	.26				.04	
630.8	635.9	82284	5.1	4.8	2A0	2.86	.07	.91	1.84	19.91		.07	4	2	7	.32				.02	
635.9	641.0	82285	5.1	5.1	2A0	2.23	21.07	.98	2.53	24.26		.04	6	1	7	.35				.03	
641.0	646.1	82286	5.1	5.1	2A4	2.99	.09	1.70	4.22	32.66		.07	9	1	11	.37				.04	
646.1	651.2	82287	5.1	5.1	2A0	2.15	.08	.50	.93	15.24		.04	3	2	6	.49				.05	
672.0	676.5	82288	4.5	4.5	2A1	2.25	21.07	.88	1.86	14.00		.04	5	4	9	.24				.06	
676.5	681.0	82289	4.5	4.1	2A41	2.62	.18	2.71	6.50	53.50		.07	10	13	23	.12				.03	

.36

.35

11.7

-2.33

DDH: 82F-16

---DEPTHS---				-----ASSAYS-----																
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
631.0	635.1	82290	4.1	4.1	2A0	2.17	.08	.47	.65	9.64				4	3	8	.17			.08
635.1	639.2	82291	4.1	3.6	2A0	2.73	.05	.15	.19	7.15				2	3	5	.51			.17
639.2	643.3	82292	4.1	4.1	2A4	2.79	.06	1.44	2.70	37.32				2	3	5	.19			.03
643.3	645.5	82293	2.2	2.2	2G4	4.15	.05	3.35	7.37	48.43				2	12	15	20.77			.09
645.5	649.6	82294	4.1	4.1	2E4	4.06	.29	5.68	8.11	89.58				.07	12	17	29	.68		.20
649.6	653.7	82295	4.1	4.1	2E4	4.32	.15	5.82	8.36	87.40				.04	6	20	27	.20		.23
653.7	657.8	82296	4.1	4.1	2E4	4.36	.20	7.36	7.38	111.35				.07	7	21	29	.30		.18
657.8	662.0	82297	4.2	4.2	2A4	2.77	.06	1.50	3.21	27.68				.34	2	4	6	.15		.01
662.0	666.3	82298	4.3	4.3	2A0	2.77	.02	.63	1.62	12.44				.14	1	2	4	.14		.01
666.3	670.6	82299	4.3	4.3	2A0	2.81	.05	1.26	2.54	30.79				.21	3	3	7	.45		.01
670.6	676.4	82300	5.8	5.7	2A47	3.80	.36	3.15	6.34	79.00				.04	30		30	.06		.04
676.4	682.0	82301	5.6	5.6	2A0	2.74	.05	.60	1.23	16.17					3	2	5	.15		.03

14.5
0.19, 5.84, 7.86, 88.88

DDH: 82F-17

						-----ASSAYS-----																
---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT	BAO %	Hg %	Mn %	As %	Ba %	S.G.	
FROM	TO														Fe						W.R.	
298.8	301.0	82302	2.2	2.2	2A0	2.81	.15	.03	.10	7.47					3	2	6	.53			.04	
301.0	305.5	82303	4.5	4.5	2D5	3.33	23.20	2.03	6.69	23.64					.21	6	12	18	.05		.09	
305.5	310.0	82304	4.5	4.5	2D5	3.37	.08	5.03	10.16	38.26					.21	4	8	13	.09		.05	
310.0	315.6	82305	5.6	5.6	2E42	4.44	.16	5.09	4.61	71.54					.07	9	19	29	.06		.24	
315.6	321.2	82306	5.6	4.4	2E42	4.48	50.31	5.05	5.24	97.36					.04	16	13	29	.10		.39	
321.2	326.8	82307	5.6	5.6	2E42	4.45	.18	2.65	3.88	40.44					.04	9	20	29	.03		.15	
326.8	331.0	82308	4.2	4.2	2A41	2.98	.17	1.28	4.54	22.71					.07	5	3	8	.18		.05	
331.0	335.1	82309	4.1	4.1	2A1	2.79	.12	.93	1.93	18.04					.01	3	2	5	.45		.02	
335.1	339.2	82310	4.1	3.8	2A1	2.61	.03	.29	1.29	7.15						1		2	.68		.01	
339.2	344.2	82311	5.0	5.0	2A0	2.80	.06	.08	.32	4.98						3	3	7	.53		.03	
344.2	349.2	82312	5.0	5.0	2A0	2.79	21.14	.08	.89	9.02						6		7	.30		.07	
349.2	354.2	82313	5.0	5.0	2A0	2.85	.13	1.42	.99	31.10						5	2	8	.32		.05	

25.81 }
 0.19, 4.01, 5.92, 8.23 }
 1.22 }

DDH: 82F-22

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													S.G. W.R.
FROM	TO						CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	
324.8	328.8	82314	4.0	3.5	2C5	2.91	.08	.16	.85	14.93				7	1	8	.75		.04	
328.8	330.5	82315	1.7	1.7	2E41	3.41	.16	2.44	6.42	42.61				8	9	17	.14		.04	
330.5	333.2	82316	2.7	2.7	2C0	3.10	.13	1.49	6.07	34.84				6	2	9	.20		.03	
333.2	335.5	82317	2.3	2.3	2E0	3.47	.16	1.85	5.04	39.81				7	10	17	.57		.02	
335.5	340.5	82318	5.0	4.0	2A0	2.75	.09	.16	.55	16.17				3	2	5	.26		.01	
342.2	343.4	82319	1.2	1.2	2E41	3.68	.21	1.40	7.20	96.42				11	12	23	.21		.03	
343.4	347.2	82320	3.8	2.8	2D0	3.19	.09	1.31	6.56	38.59				6	5	11	.27		.02	
347.2	351.2	82321	4.0	2.8	2C0	2.19	.12	.22	.45	13.69				2		3	.14		.02	

DDH: 82F-24

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													S.G. W.R.
FROM	TO						CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	
32.0	35.5	82322	3.5	2.0	2E46	5.00	1.05	5.99	.82	102.02		.69	26	26	5.10		.02			
35.5	39.0	82323	3.5	1.8	2E46	4.54	.35	7.63	4.02	131.57		.55	1	20	21	6.73		.12		
39.0	45.0	82324	6.0	.8	2D06	3.08	.68	2.69	3.91	54.12		.17	1	5	6	3.87		.08		
45.0	48.0	82325	3.0	.2	2G0	3.20	.20	.28	4.57	15.24		.04	1	3	4	23.71		.10		
48.0	54.0	82326	6.0	2.3	2C0	2.87	.35	3.32	4.25	35.77		.07	1		2	2.43		.04		
54.0	60.0	82327	6.0	5.1	2A4	4.10	.14	4.41	5.23	55.99		.21	1	1	3	1.44		.02		
60.0	65.0	82328	5.0	5.0	2A4	2.86	.12	1.81	3.04	30.79		.07		3	4	.34		.01		
65.0	70.0	82329	5.0	5.0	2A4	2.92	.13	1.76	3.50	27.68		.07	1	3	4	2.83		.03		
70.0	75.5	82330	5.5	5.0	2A4	2.78	.10	3.53	1.22	53.19		.21		1	2	.60		.01		
82.0	87.0	82331	5.0	3.8	2A0	2.65	.08	.71	1.33	25.19		.07	8	1	9	.81		.04		
87.0	90.0	82332	3.0	3.0	2A0	2.67	.08	.66	.99	18.04			1	2	3	.52		.01		
90.0	94.5	82333	4.5	4.5	2A0	2.17	.03	.66	1.16	16.17			1	2	3	.49		.04		

DDH: 83F-01

-----DEPTHS-----				-----ASSAYS-----																
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
568.0	569.2	82350	1.2	1.0	2E4	3.02	.12	2.43	4.27	30.17		.14	5	6	11	.20				.10
569.2	575.0	82351	5.8	5.8	2A0	2.68	.03	.69	1.70	14.00		.13	1		1	.36				.02
575.0	580.1	82352	5.1	5.1	2A0	2.74	.06	.79	1.15	22.08		.29	2	1	3	.29				.07
580.1	584.3	82353	4.2	3.4	2A4	2.70	.05	3.14	3.56	65.94 ←		.41	2	1	3	.28				.05
584.3	586.9	82354	2.6	2.5	2L0	2.74	.07	.16	.26	6.53		.02	3	3	7	.94				.14

DDH: 83F-02

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													S.G. W.R.
FROM	TO						CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	
721.6	723.7	82355	2.1	2.1	2A3	3.10	.20	.35	1.70	11.20			.33	7	8	16	.20		.04	
723.7	726.3	82356	2.6	2.6	2A4	3.00	.14	2.18	4.50	38.88			.21	4	5	10	.19		.02	
726.3	728.3	82357	2.0	2.0	2A0	2.80	.05	1.26	1.85	42.30			.90	1		2	.68		.02	
728.3	730.4	82358	2.1	2.1	2H46	4.20	.21	5.32	8.12	88.33			.16	17	10	28	5.98		.14	
730.4	737.0	82359	6.6	6.6	2E64	4.10	.10	4.29	6.78	61.90			.09	5	17	22	4.94		.10	
737.0	738.4	82360	1.4	1.4	2Q4&	3.52	.38	4.88	3.11	87.40			.22	6	10	17	3.33		.11	
738.4	739.9	82361	1.5	1.3	2E46	4.46	.08	5.83	6.64	92.69			.11	4	22	26	5.85		.22	
739.9	743.0	82362	3.1	3.1	2D6	3.29	.10	2.92	4.72	42.61			.12	3	9	12	5.25		.06	
743.0	745.7	82363	2.7	2.6	2D64	3.52	.19	6.09	4.54	111.04			.38	4	11	15	12.05		.09	
745.7	749.9	82364	4.2	4.2	2G4	4.51	.22	4.64	5.80	67.81			.12	5	19	24	12.15		.22	
749.9	751.6	82365	1.7	1.7	2D36	4.15	.24	3.25	4.27	56.92			.17	5	16	22	15.74		.28	
751.6	755.6	82366	4.0	4.0	2G4	4.58	.22	4.72	4.99	84.91			.21	6	21	27	6.36		.27	
755.6	759.3	82367	3.7	3.4	2G4	4.67	.17	5.56	6.31	94.87			.18	6	19	26	8.98		.26	
759.3	762.6	82368	3.3	3.3	2E41	4.23	.09	4.91	8.67	55.36			.20	5	20	26	.22		.07	
762.6	764.4	82369	1.8	1.7	2D5	3.01	.08	1.69	5.93	17.11			.20	3	3	7	.27		.06	
764.4	769.4	82370	5.0	4.9	2A41	2.87	.13	1.03	2.89	21.15			.20	3	4	8	.24		.03	
769.4	773.2	82371	3.8	3.8	2A41	2.79	.07	1.40	3.25	20.53			.19	3	2	6	.40		.06	
773.2	778.0	82372	4.8	4.6	2A41	2.76	.03	1.08	2.89	13.38			.20	1	3	5	.35		.03	
778.0	782.7	82373	4.7	4.7	2A41	2.78	.04	.96	2.61	17.11			.21	1	6	7	.31		.04	
782.7	787.0	82374	4.3	4.3	2A0	2.76	.02	.74	1.88	12.13			.19	1	1	2	.40		.01	
787.0	791.9	82375	4.9	4.3	2A0	2.66	.02	1.30	2.46	23.02			.13	2		3	.27		.04	

DDH: 83F-04

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													S.G. W.R.
FROM	TO						CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAD %	Hg %	Mn %	As %	
696.6	699.2	82376	2.6	2.6	1D4	2.81	.02	.33	.60	3.11			.05	2	2	4	.33		.07	
699.2	703.2	82377	4.0	4.0	2A4	2.94	.05	1.34	3.05	23.95			.20	1	5	6	.22		.03	
703.2	707.6	82378	4.4	4.4	2E41	3.61	.09	1.86	4.80	45.10			.21	2	19	22	.19		.04	
707.6	710.5	82379	2.9	2.9	2E4	3.90	.14	5.47	8.83	95.49			.09	7	16	24	.19		.15	
710.5	712.3	82380	1.8	1.6	2D0	2.88	.07	2.09	2.98	46.66			.12	3	3	6	.36		.03	
712.3	716.4	82381	4.1	4.0	2D5	2.87	.06	1.04	2.64	35.77			.15	3	4	7	.27		.04	
716.4	720.1	82382	3.7	3.7	2A14	2.82	.06	2.45	2.47	66.87			.26	5	2	7	.32		.06	
720.1	723.8	82383	3.7	3.7	2A14	2.79	.06	1.39	2.89	40.12			.24	2	2	5	.27		.03	
725.0	777.0	82384	2.0	2.0	2D0	2.89	.07	1.29	3.57	44.79			.01	7	1	9	.34		.09	
789.6	790.8	82385	1.2	1.2	0Q9	2.86	.05	.09	.17	5.29			.03	4	4	9	.38		.07	
792.8	793.5	82386	.7	.7	0Q9	2.92	.04	.12	.16	6.22			.01	7	3	10	.43		.09	
794.5	795.6	82387	1.1	1.1	0Q9	2.96	.05	.03	.07	4.98			.01	5	4	10	.29		.08	

Hole outside integrated limit

DDH: 83F-07

---DEPTHS---		SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	---ASSAYS---					Hg %	Mn %	As %	Ba %	S.G. W.R.	
FROM	TO											TOT Fe	BAO %	Po %	Py %							
52.0	61.0	82388	9.0	2.3	2G4	4.41	5.23	5.80	83.05		.19	3	19	23	13.13		.22					
61.0	64.5	82389	3.5	.7	2G4	4.23	4.69	5.81	58.16		.12	4	18	23	14.34		.28					
64.5	68.0	82390	3.5	3.5	2A41	2.78	1.50	3.35	22.08		.07		2	2	.56		.01					
68.0	72.0	82391	4.0	4.0	2A41	2.80	2.10	4.00	28.62		.07	1	3	4	.73		.02					
72.0	76.0	82392	4.0	3.8	2A41	2.73	2.28	4.05	25.19		.10	1	1	2	.66		.01					
76.0	80.0	82393	4.0	3.2	2A41	2.74	1.27	3.67	14.93		.10	2	2	4	.35		.02					
80.0	87.0	82394	7.0	2.2	2A41	2.72	2.51	6.51	28.62		.19	2	1	3	.32		.05					
87.0	90.4	82395	3.4	3.4	2A41	2.67	1.27	4.01	18.35		.11	2	2	4	.56		.02					
90.4	97.0	82396	6.6	6.6	2A1	2.65	.56	1.18	12.75		.08	2	1	3	.53		.01					

DDH: 83F-08

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														S.G. W.R.
FROM	TO						CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %	
632.6	636.4	82397	3.8	3.8	2A41	2.74	.05	1.03	3.08	13.69		.09	2	4	6	.25		.06			
636.4	641.5	82398	5.1	5.1	2E4	3.87	.16	4.63	6.89	80.56		.13	6	14	21	7.01		.14			
641.5	645.5	82399	4.0	4.0	2A4&	2.70	.02	.65	1.68	12.75		.51	1	1	3	.29		.03			
645.5	648.2	82400	2.7	2.7	2D0	3.28	.07	3.28	6.85	53.81		.18	4	9	14	.32		.05			
648.2	652.0	82401	3.8	3.7	2A1	2.72	.04	1.33	2.23	26.44		.13	2	2	4	.29		.03			
652.0	655.0	82402	3.0	3.0	2A1	2.70	.02	.69	1.70	19.60		.51	1	1	3	.26		.03			

hole is outside limit - interpreted

DDH: 83F-09

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													S.G. W.R.
FROM	TO						CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	
238.4	240.6	82403	2.2	2.1	2A0	2.79	.05	.25	.41	11.82		.11	5	3	8	.19		.17		

20

DDH: 83F-10

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													S.G. W.R.		
FROM	TO						CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %		Ba %	
352.1	355.3	82404	3.2	3.2	2L0&	2.82	.04	.35	.35	8.71		.02	2	3	5	.27		.06				
355.3	359.3	82405	4.0	4.0	2A0	2.79	.09	.74	1.79	18.05		.21	2	4	6	.19		.03				
359.3	364.9	82406	5.6	5.6	2A0&	2.82	.05	.65	2.36	17.11		.15	1	3	4	.20		.01				
364.9	370.5	82407	5.6	5.6	2A0&	2.77	.03	1.02	2.61	12.75		.25	1	3	4	.22		.01				
370.5	375.8	82408	5.3	5.2	2A0	2.75	.03	.98	2.48	23.02		.23	1	3	4	.26		.01				
375.8	381.0	82409	5.2	5.2	2A0	2.80	.02	.92	2.29	23.01		.16	1	4	6	.23		.01				
381.0	386.7	82410	5.7	5.7	2A0	2.69	.02	.44	.74	12.13		.11	1	1	2	.88		.03				
386.7	392.4	82411	5.7	5.6	2A0	2.66	.02	.47	.85	8.71		.14		1	2	.87		.01				
392.4	395.7	82412	3.3	3.3	2A0	2.79	.05	.53	1.19	5.60		.19	1	4	6	.75		.02				
395.7	399.1	82413	3.4	3.4	2A0	2.72	.02	.26	.38	3.11		.04	2	1	4	.73		.04				

DDH: 83F-11

-----DEPTHS-----				-----ASSAYS-----																
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
39.0	40.8	82414	1.8	1.7	2A43	3.03	.05	4.90	9.65	25.19	.22	1	7	9	.15		.01			
40.8	44.0	82415	3.2	2.2	2D0	3.04	.22	.88	2.03	13.38	.16	3	9	13	.27		.02			
44.0	47.0	82416	3.0	3.0	2D0	3.01	.22	1.00	1.98	18.97	.16	3	9	13	.42		.03			
47.0	52.0	82417	5.0	.2	2D0	2.90	.12	.54	.96	10.58	.11	2	6	9	.62		.02			
52.0	56.0	82418	4.0	1.2	2E64	4.32	.29	7.40	6.71	142.14	.63	2	22	25	5.69		.26			
56.0	62.0	82419	6.0	.6	2E64	4.31	.36	8.08	6.69	146.19	.80	8	20	29	4.83		.34			
62.0	67.0	82420	5.0	4.0	2E64	4.31	.36	6.72	5.30	121.30	.26	8	22	30	3.07		.19			
67.0	72.0	82421	5.0	4.6	2E64	4.32	.21	6.34	6.80	88.33	.23	8	19	27	7.78		.17			
72.0	77.0	82422	5.0	3.9	2E64	4.28	.23	6.22	5.38	124.73	.53	10	20	30	4.74		.22			
77.0	80.0	82423	3.0	.8	2G0	4.47	.20	4.08	4.26	72.47	.58	2	22	25	15.26		.17			
80.0	85.0	82424	5.0	4.5	2G4	4.24	.20	5.08	5.11	59.10	.20	2	19	22	17.42		.18			
85.0	90.2	82425	5.2	4.5	2G4	4.11	.23	5.41	5.74	75.58	.14	2	22	24	10.62		.19			
90.2	95.0	82426	4.8	2.2	2A4	2.80	.05	1.71	3.23	21.46	.26		2	2	.87		.01			
95.0	100.0	82427	5.0	5.0	2A4	2.80	.05	1.35	3.24	27.37	.08	1	2	4	.76		.01			
100.0	105.0	82428	5.0	3.4	2A0	2.85	.05	.95	2.33	22.71	.08	1	3	4	.60		.01			
105.0	110.0	82429	5.0	4.0	2A0	2.72	.05	.89	1.98	24.88	.11	2	2	4	.77		.02			
110.0	116.0	82430	6.0	3.1	2A0	2.72	.03	.49	.91	20.22	.11	2	1	4	.41		.05			

DDH: 83F-12

-----DEPTHS-----				-----ASSAYS-----																
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
736.6	738.6	82431	2.0	2H41	3.89	.19	5.12	8.79	82.11		.14	13	14	28	.40		.13			
738.6	742.2	82432	3.6	2E41	4.22	.11	5.50	9.53	81.49		.13	7	22	29	.18		.11			
742.2	744.2	82433	2.0	2E44	3.96	.11	4.66	8.69	74.65		.13	4	21	26	.43		.09			
744.2	748.0	82434	3.8	2E4	4.25	.17	4.37	8.05	65.01		.12	7	23	30	.59		.27			
748.0	752.2	82435	4.2	2E4	3.87	.14	3.94	7.63	62.52		.25	6	19	25	.27		.13			
752.2	755.5	82436	3.3	2A34	3.19	.05	2.20	5.96	32.66		.41	3	10	14	.32		.04			
755.5	760.0	82437	4.5	2A34	2.94	.11	2.03	3.41	52.25		.65	4	4	9	.32		.04			
760.0	764.7	82438	4.7	2A34	2.79	.13	1.26	3.15	37.64	1.60		3	12	15	.26		.03			

18.91
 0.13, 0.22, 8.02, 1.54, 2.78

DDH: 83F-14

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														S.G. U.R.	
FROM	TO						CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %		
9.7	15.0	82439	5.3	.9	2A07	2.62	.01	.20	.37	9.64							.05			.56		.01
15.0	22.0	82440	7.0	.7	2A07	2.60	<i>20</i> .01	.25	.16	8.71							.03			.48		.01
22.0	26.0	82441	4.0	.4	2A07	2.60	.06	.38	.40	8.09							.05			.66		.01
26.0	30.0	82442	4.0	.4	2A0	2.60	.05	.51	.41	15.24							.14	1	1	.29		.01
30.0	34.0	82443	4.0	1.4	2A0	2.69	<i>20</i> .11	.58	1.33	15.86							.12	1	2	.42		.01
34.0	38.2	82444	4.2	1.4	2A0	2.67	.11	.88	1.93	21.46							.10		1	.59		.02
38.2	40.3	82445	2.1	2.1	2A1	2.67	.03	.37	.42	11.20							.05	2	1	.50		.02
<i>white</i> 40.3	42.0	82446	1.7	1.7	2A11	2.83	.02	.31	.91	6.84							.29	4	2	.22		.16
46.5	98.1	82447	1.6	1.4	0Q9	2.85	.12	.30	.63	17.73							.01	3	5	.19		.03
98.1	102.8	82448	4.7	3.8	2A0	2.67	<i>white</i> .04	.41	1.29	14.93							.05	1	1	.55		.03
102.8	107.4	82449	4.6	4.6	2A0	2.70	.04	.37	.78	16.80							.47	1	1	.77		.03
107.4	108.5	82450	1.1	1.1	0Q9	3.27	.10	12.03	.26	660.33							.07	2	7	10	.24	.03

DDH: 83F-15

-----DEPTHS-----					-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
641.4	647.0	82451	5.6	2A4	2.94	11	2.36	3.95	29.24						.20					.02
647.0	652.7	82452	5.7	2D0	2.90	10	3.88	2.08	50.08						.32					.02
652.7	654.8	82453	2.1	2E46	4.33	.03	4.34	12.32	59.41						4.60					.05
654.8	660.6	82454	5.8	2G41	4.28	.12	4.55	7.50	74.65						14.17					.20
660.6	662.3	82455	1.7	2D4	3.72	.17	4.78	5.08	67.50						10.53					.15
662.3	666.5	82456	4.2	2F46	3.84	.19	4.49	6.85	87.10						4.03					.16
666.5	669.8	82457	3.3	2E48	4.51	.10	2.48	5.96	48.21						.19					.05
669.8	675.2	82458	5.4	2A41	3.03	.05	1.74	4.41	24.37						.36					.02
675.2	680.5	82459	5.3	2A41	2.81	.06	1.07	2.88	21.15						.27					.01
680.5	684.0	82460	3.5	2A38	2.90	.10	1.06	2.51	29.55						.25					.01
684.0	687.4	82461	3.4	2A0	2.82	.05	.53	1.75	9.95						.24					.01
687.4	689.4	82462	2.0	2A1	2.75	.06	.52	1.55	15.55						.22					.02
689.4	692.6	82463	3.2	2D5	2.87	.05	.97	2.73	24.26						.28					.04
692.6	695.7	82464	3.1	2D5	3.09	.14	1.60	3.50	34.34						.35					.03
695.7	700.0	82465	4.3	2A1	2.79	.05	.80	2.02	17.42						.21					.01
700.0	704.3	82466	4.3	2A1	2.82	.06	.91	2.04	29.55						.20					.04
704.3	708.6	82467	4.3	2A1	2.78	.03	.66	2.08	15.55						.34					.02
708.6	709.7	82468	1.1	2C0	2.85	.05	.62	.77	18.35						.26					.13

Handwritten notes:
 23, 28, 60, 21,
 0.12, 3.73, 5.65, 57.98

DDH: 83F-16

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														S.G. W.R.
FROM	TO						CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %	
15.0	20.0	82469	5.0	5.0	2A0	2.67	.14	1.28	.54	15.55		.02			1	.77					
20.0	21.4	82470	1.4	1.4	2A0	2.69	.18	1.44	1.25	12.75		.01		1	1	.79					
21.4	25.0	82471	3.6	3.6	2A1	2.71	.12	1.30	1.44	12.13		.02	1	1	3	.72					.01
25.0	28.9	82472	3.9	3.9	2L4	2.68	.13	.68	.47	8.71		.01	3		4	.77					.02
28.9	33.8	82473	4.9	4.9	2A1	2.73	.11	.48	.73	10.25		.02	2	2	5	.87					.01
33.8	37.5	82474	3.7	3.7	2A0	2.71	.04	.61	.63	9.02		.04	1	2	3	.60					.03
37.5	39.0	82475	1.5	1.5	2A4	2.86	.05	.74	1.09	8.09		.02	3	3	6	.35					.11
39.0	44.0	82476	5.0	5.0	2L4	2.75	.02	.40	.84	5.60		.04	3		4	.56					.09
68.0	72.0	82477	4.0	3.4	2A0	2.78	.04	.62	.68	9.64		.02	4	1	5	.67					.09
72.0	77.0	82478	5.0	5.0	2A0	2.77	.04	.76	1.91	14.31		.12	2	1	4	.72					.03
77.0	81.5	82479	4.5	4.4	2A0	2.80	.04	.64	1.95	18.04		.10	3	2	5	.75					.03
81.5	86.0	82480	4.5	4.3	2D5	2.94	.05	1.68	3.10	35.77		.09	4	3	8	.53					.05
86.0	90.0	82481	4.0	3.4	2A1	2.82	.04	.93	2.13	16.49		.07	3	1	5	.66					.04
90.0	95.0	82482	5.0	5.0	2D5	2.88	.07	1.18	2.54	18.66		.14	3	3	7	.34					.05
95.0	100.6	82483	5.6	5.4	2L4	2.88	.05	.97	2.42	18.35		.01	5	3	9	.39					.08
100.6	102.7	82484	2.1	2.0	2A0	2.82	.06	.29	.74	6.84		.01	3	3	7	.29					.04
109.2	109.8	82485	.6	.6	2E34	3.50	.08	3.64	6.54	73.72		.05	5	18	23	.19					.17

DDH: 83F-17

---DEPTHS---				-----ASSAYS-----																	
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %	S.G. W.R.	
9.5	12.0	82486	2.5	2.5	2A0	2.66	.03	1.01	.12	21.77						1.04					.01
12.0	15.0	82487	3.0	3.0	2A0	2.64	.02	.80	.08	10.26						1.03					
15.0	19.0	82488	4.0	4.0	2A0	2.61	.02	.63	.12	12.44						1.37					
19.0	24.0	82489	5.0	5.0	2A0	2.62	.05	.56	.10	9.95						1.13					
24.0	29.0	82490	5.0	5.0	2A0	2.67	.07	.73	.45	15.86				1		1.02					
29.0	31.8	82491	2.8	2.8	2A0	2.70	.05	.49	.50	7.78				1		.70					

DDH: 83F-18

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														S.G. W.R.
FROM	TO						CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %	
24.0	28.5	82492	4.5	.9	2L07	2.66	.03	.76	.30	44.79		.80	4		4	.70		.01			
28.5	31.2	82493	2.7	2.7	1E19	2.70	.01	.20	.09	9.02		.31		3	4	.25		.01			
31.2	36.0	82494	4.8	4.8	2F4	3.12	.10	6.84	8.18	44.48		.27	1	5	7	.33		.01			
36.0	40.4	82495	4.4	4.2	2G4	4.45	.25	5.50	4.53	93.93		.24		23	24	11.63		.11			
40.4	42.0	82496	1.6	1.6	2G4	4.25	.18	3.84	6.28	72.16		.18	3	17	20	18.74		.20			
42.0	47.0	82497	5.0	5.0	2H4	4.32	.35	5.68	6.72	108.86		.38	13	17	31	8.63		.31			
47.0	51.5	82498	4.5	4.5	2H4	4.54	.21	4.66	5.78	84.60		.58	10	21	31	8.41		.34			
51.5	57.5	82499	6.0	6.0	2H4	4.40	.27	5.60	6.24	84.60		.41	18	11	30	8.46		.38			
57.5	61.4	82500	3.9	3.9	2E46	4.22	.23	4.62	5.09	75.29		.22	9	22	31	4.16		.30			
61.4	65.0	82501	3.6	3.6	2D6	3.43	.07	2.82	4.00	51.32		.34	2	13	16	9.11		.11			
65.0	69.7	82502	4.7	4.7	2B46	3.04	.23	2.66	1.67	39.19		.22	2	5	8	8.64		.06			
69.7	72.9	82503	3.2	3.2	2E46	4.28	.14	5.91	5.48	78.69		.21	4	24	29	5.15		.18			
72.9	74.0	82504	1.1	1.1	2A14	3.05	.08	5.60	6.30	57.23		.34	1	2	4	1.22		.03			
74.0	80.4	82505	6.4	6.4	2A0	2.80	.05	1.14	1.87	25.82		.58		1	2	1.18		.01			
80.4	84.9	82506	4.5	4.5	2D5	2.82	.05	1.72	3.00	26.75		.20	1	1	3	.69		.02			
84.9	90.2	82507	5.3	5.3	2D0&	2.85	.06	1.44	2.38	32.04		.24		2	3	.73		.01			
90.2	95.0	82508	4.8	4.8	2A4	2.86	.04	1.35	2.53	30.17		.38	1	2	3	.73		.01			
95.0	99.2	82509	4.2	4.2	2A4	2.80	.03	1.16	2.79	21.15		.25		3	4	.68		.01			
99.2	103.5	82510	4.3	4.3	2A0	2.83	.08	.90	2.28	17.11		.26	1	4	5	.90		.01			
103.5	107.8	82511	4.3	4.3	2A0	2.75	.04	.49	.76	15.86		.14	1	1	3	.68		.01			
107.8	109.5	82512	1.7	1.7	2A0&	2.77	.02	1.62	2.20	31.10		.14	1		2	.55		.05			

DDH: 83F-19

---DEPTHS---				-----ASSAYS-----																	
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %	S.G. U.R.	
694.5	697.9	82513	3.4	3.4	2A41	2.74	.04	.85	2.51	20.84					.25		.05				
697.9	699.5	82514	1.6	1.6	2D4	3.23	.11	4.84	7.16	68.12					.20		.08				
699.5	704.1	82515	4.6	4.6	2E41	3.66	.18	6.47	10.64	96.11					.18		.14				
704.1	708.7	82516	4.6	4.6	2E41	3.38	.09	8.57	16.20	114.15					.14		.15				
708.7	713.2	82517	4.5	4.0	2E46	3.51	.12	7.51	13.90	101.71					1.35		.16				
713.2	717.5	82518	4.3	4.3	2H41	3.87	.22	5.96	11.00	90.82					1.65		.15				
717.5	721.8	82519	4.3	4.3	2H41	3.72	.26	4.00	8.97	66.56					.61		.11				
721.8	726.0	82520	4.2	4.2	2H41	3.63	.20	5.13	10.16	78.38					.81		.08				
726.0	728.0	82521	2.0	1.4	2E41	3.83	.06	4.08	7.81	45.10					.20		.05				
728.0	732.7	82522	4.7	4.3	2A43	2.82	.07	1.06	2.70	21.46					.21		.02				
732.7	735.9	82523	3.2	3.2	2A0	2.76	.07	.64	1.46	16.80					.22		.02				

30.1
0.17, 6.09, 11.35, 27.38

DDH: 83F-20

-----DEPTHS-----				-----ASSAYS-----																	
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %	S.G. W.R.	
116.5	122.0	82524	5.5	5.5	2A0	2.79	.04	.72	1.45	15.24	.10	3	1	4	.36		.11				

DDH: 83F-22

---DEPTHS---				-----ASSAYS-----																
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
834.4	838.0	33501	3.6	3.3	2A41	2.87	.03	2.16	2.94	27.37					.14					.05
838.0	842.4	33502	4.4	3.4	2A1	2.93	.06	1.16	2.77	25.82					.18					.03
842.4	843.0	33503	.6	.6	2D4	3.45	.11	6.96	11.03	118.82					.09					.09
843.0	845.3	33504	2.3	2.0	2H41	3.91	.20	4.65	7.85	94.24					.20					.09
845.3	846.3	33505	1.0	1.0	2A41	3.17	.06	2.57	4.46	37.95					.28					.06
846.3	848.9	33506	2.6	2.5	2F4&	4.41	.09	3.50	7.70	46.66					.10					.03
848.9	851.8	33507	2.9	2.9	2D05	2.99	.06	1.58	3.51	25.50					.25					.02
851.8	855.4	33508	3.6	3.6	2A1&	2.85	.05	.80	2.26	17.42					.14					.02
855.4	860.0	33509	4.6	4.6	2A1&	2.81	.04	1.03	2.41	18.66					.11					.02
860.0	865.1	33510	5.1	4.9	2A1&	2.99	.07	.97	2.79	23.64					.16					.02
865.1	868.1	33511	3.0	3.0	2Q0	3.05	.13	1.65	2.58	53.19					.14					.03

9.4
3.31, 6.31, 55.45

9.4
3.31, 6.31

DDH: 84F-01

					-----ASSAYS-----														
---DEPTHS---	SAMPLE INT. REC. ROCK S.G. CU Pb Zn Ag(AA) Ag(FA) Au(FA) Po Py TOT BAO Hg Mn As Ba S.G.	FROM TO NO. UNIT PULP % % % g/mT g/mT g/mT % % Fe % % % % W.R.																	
283.0	286.3	33512	3.3	3.3	2C39	3.21	.50	.20	.29	10.89		.20	6	11	18	.23	.03		
286.3	291.2	33513	4.9	4.9	2D09	3.44 ³³	.27	2.49	6.08	36.70		.30	5	10	15	.14	.07		
291.2	295.7	33514	4.5	4.5	2D49	3.61	.30	4.19	10.95	59.72		.30	13	4	17	.37	.16		
295.7	301.5	33515	5.8	5.6	2G4	4.50	.17	5.34	5.88	88.25		.20	6	19	26	11.50	.38		
301.5	305.7	33516	4.2	4.2	2G4	4.69 ⁶⁰	.22	5.32	5.98	71.54		.30	6	17	23	15.00	.35		
305.7	308.9	33517	3.2	3.2	2G4	4.65	.19	5.62	5.88	88.33		.40	6	19	26	13.51	.32		
308.9	312.2	33518	3.3	3.2	2E46	4.31	.26	5.09	6.65	94.56		.20	15	12	27	6.23	.30		
312.2	317.4	33519	5.2	5.2	2L2	2.99 ^{write}	.09	1.20	1.55	31.10		.30	3	3	7	4.51	.09		
317.4	322.6	33520	5.2	4.2	2B06	2.96	.05	.82	1.11	20.84		.10	3	1	4	6.38	.07		
322.6	326.8	33521	4.2	4.2	2B06	2.88 ³²	.06	.81	.50	32.04		.28	2	2	5	5.91	.07		
326.8	330.0	33522	3.2	3.0	2B06	3.24	.11	2.84	2.76	78.38		.20	6	4	11	8.20	.16		
330.0	335.6	33523	5.6	5.6	2E14	3.54 ⁶⁰	.18	2.97	3.12	55.99		.20	8	10	19	3.65	.18		
364.2	367.5	33524	3.3	3.3	2D09	3.21 ³²	.26	3.79	2.43	330.64		18.36	6	5	11	4.59	.14	.63	
367.5	372.0	33525	4.5	4.5	2E46	4.68	.19	4.90	6.15	53.81		.10	3	24	27	6.74	.08		
372.0	375.0	33526	3.0	3.0	2G4	4.53 ⁶⁰	.10	5.07	7.87	53.50		.01	2	12	15	28.29	.09		
375.0	380.1	33527	5.1	5.1	2E09	4.60	.58	2.95	4.94	31.10		.01	5	27	32	.34	.12		
380.1	385.0	33528	4.9	4.7	2E09	4.69	.32	4.59	7.83	38.57		.10	4	26	30	.06	.10		
385.0	389.9	33529	4.9	4.9	2E4	4.77 ⁵⁰	.14	4.23	7.05	25.50		.10	3	27	31	.02	.08		
389.9	391.5	33530	1.6	1.6	2E4	4.63	.16	6.09	9.77	41.68		.01	4	25	29	.11	.10		
391.5	397.0	33531	5.5	4.9	2E4	4.76	.28	2.57	2.01	41.99		.10	2	31	34	.02	.09		
397.0	403.4	33532	6.4	5.8	2E4	4.35	.10	3.74	3.53	55.05		.10	2	27	30	.03	.10		
403.4	407.0	33533	3.6	3.6	2E0&	4.66	.13	2.07	1.48	22.39		.01	2	32	35	.02	.06		
407.0	412.3	33534	5.3	4.6	2E4&	4.52 ⁵⁰	.14	2.61	2.05	20.22		.10	3	29	32	.01	.07		
412.3	416.4	33535	4.1	4.1	2E4&	4.51	.18	2.58	2.30	21.15		.01	3	29	32	.01	.09		
416.4	421.4	33536	5.0	4.8	2E4&	4.68	.30	1.35	2.84	13.37		.01	3	30	34	.01	.09		
421.4	425.2	33537	3.8	3.8	2E0&	4.43	.22	2.15	1.46	19.28		.10	3	28	31	.01	.09		
425.2	430.1	33538	4.9	4.9	2E42	4.80 ⁵⁰	.16	2.88	4.60	22.70		.01	3	30	33	.01	.06		
430.1	433.9	33539	3.8	3.8	2E42	4.92	.19	3.42	6.12	27.37		.01	1	30	32	.02	.02		
433.9	438.0	33540	4.1	4.1	2E42	4.81	.08	3.32	5.45	23.33		.10	1	31	32	.02	.02		
438.0	441.1	33541	3.1	3.0	2E42	4.60	.11	1.56	4.09	14.93		.01	2	30	33	.02	.04		
441.1	446.0	33542	4.9	4.9	2E09	4.60	.64	1.00	2.74	14.31		.01	5	29	34	.01	.10		
446.0	450.2	33543	4.2	3.9	2E49	4.78 ⁵⁰	.24	1.87	4.38	14.62		.01	3	30	33	.02	.06		
450.2	454.0	33544	3.8	3.7	2E4	4.73	.05	3.32	5.97	19.28		.01	2	29	32	.01	.03		
454.0	459.1	33545	5.1	5.1	2E44	4.36	.29	3.94	7.39	37.95		.10	6	23	30	.03	.07		
459.1	462.7	33546	3.6	3.6	2D09	3.17	.24	4.12	5.32	30.79		.10	5	3	9	.16	.04		
462.7	466.0	33547	3.3	3.3	2A1	2.80 ²¹	.07	1.06	2.48	13.69		.01	3	1	5	.42	.02		
466.0	468.4	33548	2.4	2.4	2D0	3.18	.16	2.21	5.60	35.77		.01	7	5	13	.13	.03		
468.4	471.3	33549	2.9	2.9	2A1	3.01	.13	.57	1.47	12.75		.01	5	5	11	.11	.05		
338.0	341.1	33600	3.1	3.1	2B0	3.04 ³²	.08	1.00	1.12	29.24		.40	2	3	6	3.84	.06		
348.2	355.0	33601	6.8	4.6	1E19	2.73	.07	.51	.42	16.17		.60	2	1	4	3.46	.07	.18	
355.0	359.6	33602	4.6	4.1	2L14	3.03 ^{Waste}	.22	1.96	6.09	94.56		4.66	4	3	7	3.26	.25	.30	
359.6	364.2	33603	4.6	4.0	2L14	3.03	.39	2.04	.91	149.61		17.56	3	5	8	3.30	.09	.91	

335.6 348.2

12.6

change to.

DDH: 84F-02

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														S.G. W.R.
FROM	TO						CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %	
778.9	781.0	33550	2.1	2.1	2L12	2.88	.03	.17	.24	5.60			.10	2	2	4	.24				.06
781.0	786.7	33551	5.7	5.7	2A4	3.00	.05	1.28	2.73	26.44			.10	3	2	5	.14				.03
786.7	789.8	33552	3.1	2.7	2D0	3.33	.15	2.42	4.42	41.37			.10	9	8	17	.15				.05
789.8	790.5	33553	.7	.7	2E43	3.84	.17	3.13	5.64	58.47			.10	13	16	29	.04				.07
790.5	793.0	33554	2.5	2.4	2D0	3.15	.13	3.58	4.84	51.32			.10	5	4	10	.15				.03
793.0	797.0	33555	4.0	4.0	2A4	2.99	.08	1.23	3.15	15.24			.10	5	5	10	.20				.03
797.0	801.6	33556	4.6	4.0	2A4	2.98	.05	1.79	3.10	22.39			.10	4	3	8	.16				.01
801.6	804.0	33557	2.4	2.4	2A0	2.90	.08	.95	2.57	21.46			.10	4	3	7	.17				.02
804.0	809.0	33558	5.0	4.6	1D49	2.73	.02	.06	.14	2.49			.10	5		5	.22				.05

Handwritten notes:
 0.14 7.286 8.72, 8.722
 6.31

DDH: 84F-03

-----DEPTHS-----				-----ASSAYS-----																
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
154.9	161.7	33559	6.8	6.6	2E14	3.70	.22	2.32	3.53	47.59					3.96		.10			.10
174.8	179.0	33560	4.2	4.2	2D39	3.54 ⁴⁰	.22	2.03	5.00	46.34					3.29		.10			.16
179.0	184.3	33561	5.3	4.2	2L2	3.17	.18	1.64	1.42	37.95					4.90		.10			.14
184.3	189.3	33562	5.0	4.9	2E49	4.23	.30	4.56	3.67	97.36					1.07		.20			.26
189.3	191.4	33563	2.1	2.1	2E4	4.70	.17	3.99	4.52	51.01					.13		.20			.05
191.4	196.0	33564	4.6	4.5	2E4&	4.32 ⁵⁰	.15	1.92	2.51	22.39					.04		.10			.14
196.0	200.0	33565	4.0	3.9	2E09	4.58	.39	1.92	2.69	38.26					.03		.10			.25
200.0	203.6	33566	3.6	3.5	2E09	4.45	.25	1.86	1.79	29.86					.08		.10			.24
203.6	206.7	33567	3.1	2.6	2E41	4.54	.17	6.65	6.13	76.20					.09		.20			.06
206.7	212.0	33568	5.3	2.6	2E0&	4.62 ⁵⁰	.26	1.97	2.18	22.08					1.01		.10			.10
212.0	216.0	33569	4.0	4.0	2E0&	4.49 ⁵⁰	.21	1.19	2.65	16.80					.03		.10			.10
216.0	220.4	33570	4.4	4.4	2E4	4.42	.17	2.14	4.23	20.84					.43		.10			.08
220.4	225.7	33571	5.3	5.3	2E89	4.41	.28	.57	1.02	3.42					.01		.10			.35
225.7	230.0	33572	4.3	4.3	2E09	4.59 ⁴⁰	.40	.30	1.16	4.66					.01		.10			.16
230.0	235.0	33573	5.0	5.0	2E4	4.45	.17	2.22	3.46	18.04					.01		.10			.06
235.0	240.4	33574	5.4	5.4	2E49	4.55 ⁵⁰	.20	3.18	6.12	18.97					.02		.10			.12
240.4	242.7	33575	2.3	2.1	2F49	4.53	.22	7.85	13.32	30.48					.02		.10			.42
242.7	247.9	33576	5.2	5.2	2E1	4.21	.13	.31	1.33	10.26					.02		.10			.03
247.9	250.4	33577	2.5	2.5	2E1	3.84 ⁴⁰	.12	.13	.84	10.89					.01		.10			.04
252.7	257.4	33578	4.7	4.7	2E89	4.03	.63	.62	2.68	11.20					.01		.10			.24
257.4	262.0	33579	4.6	4.6	2E89	4.58 ⁴⁰	.63	.48	1.80	14.31					.01		.10			.22
262.0	264.5	33580	2.5	2.5	2E89	4.33	.48	.44	2.26	7.15					.01		.10			.30
264.5	269.1	33581	4.6	4.6	2E4	4.68 ⁵⁰	.09	4.99	9.15	26.75					.01		.40			.03
269.1	272.0	33582	2.9	2.9	2D35	3.46	.11	1.16	4.95	14.00					.07		.10			.03
272.0	274.7	33583	2.7	2.7	2A1	2.96	.08	.54	1.49	16.48					.20		.20			.03
274.7	278.0	33584	3.3	3.2	2D0&	2.95 ²¹	.08	3.68	5.51	35.46					.18		.10			.04
278.0	281.3	33585	3.3	3.2	2C0&	2.41	.21	.49	1.84	14.93					.20		.20			.02
281.3	286.7	33586	5.4	5.0	2C37	3.94	.55	1.46	3.26	22.39					.10		.10			.03
286.7	289.4	33587	2.7	2.7	2C5	3.59	.06	.20	1.17	5.91					.03		.10			.01
289.4	291.9	33588	2.5	2.5	2D5	3.56	.14	2.28	4.91	35.15					.04		.10			.02
291.9	295.8	33589	3.9	3.7	2C5	3.29	.09	1.11	.74	17.73					.03		.10			.02
295.8	299.0	33590	3.2	3.2	2D4	3.42 ²¹	.08	7.39	20.60	25.50					.16		.20			.02
299.0	305.0	33591	6.0	6.0	2D4	3.38	.09	6.78	17.70	41.99					.11		.10			.08
305.0	307.0	33592	2.0	2.0	2C0	3.15	.19	.58	1.94	9.02					.15		.10			.04
307.0	309.0	33593	2.0	1.9	2A1	2.89 ²¹	.11	1.00	1.74	21.15					.25		.10			.02
309.0	314.0	33594	5.0	5.0	2A41	2.89	.07	2.80	4.24	38.26					.18		.60			.02 .15
314.0	318.7	33595	4.7	4.7	2A41	2.76	.06	1.52	4.87	23.64					.21		.40			.02 .09
318.7	324.0	33596	5.3	5.3	2A41	2.85	.06	1.51	3.18	27.37					.17		.60			.01 .14
324.0	329.5	33597	5.5	5.5	2A1	2.79 ²¹	.09	.67	2.05	15.24					.18		.20			.01
329.5	333.8	33598	4.3	4.1	2A41	2.76	.07	1.75	4.76	19.91					.17		.10			.06
250.4	252.7	33599	2.3	2.0	2E4	4.28 ⁵⁰	.19	3.11	8.48	13.06					.01		.10			.29

DDH: 84F-04

---DEPTHS---		SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													S.G. W.R.
FROM	TO					CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	
840.9	847.9	33729	7.0	7.0	2A0&	3.00	.05	1.34	3.72	21.15	10.91	.10	4	2	6	.17		.05	
847.9	850.1	33730	2.2	2.2	1F4@	2.97	.06	1.24	4.26	22.08	7.07 (20+20)	.10	8	3	12	.58		.05	
850.1	851.8	33731	1.7	1.7	2E43	3.58	.10	4.80	12.60	75.58		.10	12	7	19	1.04		.12	
851.8	854.0	33732	2.2	2.1	1F@	2.80	.05	.25	.33	5.91		.10	4	2	7	1.00		.06	
854.0	856.9	33733	2.9	2.9	2B4	2.86	.03	1.26	3.14	21.46		.10	2	1	4	.47		.02	
856.9	860.0	33734	3.1	2.8	2A14	3.02	.05	1.60	3.33	29.24		.30	4	1	6	.38		.02	
860.0	862.8	33735	2.8	2.8	2B4	2.96	.07	3.01	4.83	86.78	5.9	.80	4	2	7	.21		.04	
862.8	864.4	33736	1.6	1.6	1F4@	3.13	.11	5.21	6.43	139.97		.30	9	3	13	.11		.08	
864.4	865.9	33737	1.5	1.2	2E43	3.93	.22	6.47	8.63	206.53		.40	9	16	26	.02		.10	
865.9	868.8	33738	2.9	2.7	1F4@	2.97	.06	.80	1.81	19.91		.10	10	1	12	.16		.06	
868.8	872.2	33739	3.4	3.4	2E34	3.75	.22	1.98	3.38	49.45		.10	13	17	30	.10		.08	
872.2	875.5	33740	3.3	3.3	0Q0	2.90	.06	.11	.20	3.42		.10	3	2	6	.18		.04	
875.5	877.7	33741	2.2	2.1	2A0	2.82	.05	.85	1.66	22.39		.30	3	3	6	.13		.02	
877.7	880.1	33742	2.4	1.6	2C0	2.91	.07	.56	1.13	10.57		.30	3	3	6	.10		.03	

5.06 }
5.50 }
17.40 } 7.07

7.84 }
11.64 }
15.70 } 10.72

DDH: 84F-05

---DEPTHS---			SAMP	INT.	REC.	ROCK	S.G.	-----ASSAYS-----												S.G.	
FROM	TO	NO.						UNIT	PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe %	BAO %		Hg %
24.0	29.8	33641	5.8	5.6	2D43	3.75	33.12	3.52	6.78	69.36	.80	3	16	20	8.66						.05
29.8	33.8	33642	4.0	4.0	2L0	2.84	4.07	.36	.17	8.09	1.60	4	1	5	.69						.03
33.8	36.5	33643	2.7	2.7	2D43	3.49	33.26	4.42	10.78	101.90	.40	5	12	17	.13						.06
36.5	40.0	33644	3.5	3.5	2H49	4.21	70.56	4.25	6.97	126.90	.20	34	3	38	.03						.03
40.0	42.8	33645	2.8	2.8	2D43	3.50	33.24	4.50	9.48	125.66	.60	6	10	17	.30						.06
47.4	74.7	33646	5.3	5.3	2D3	3.45	33.12	1.98	6.29	17.11	.10	3	14	18	.90						.09
74.7	78.7	33647	4.0	4.0	2E08	4.58	50.13	1.73	2.30	18.97	.10	1	35	36	3.30						.01
78.7	79.9	33648	1.2	1.2	2F4	4.45	.05	9.27	16.90	75.27	.10	3	23	26	.06						.03
79.9	83.0	33649	3.1	3.0	2E49	4.75	.23	1.73	2.52	17.42	.10	1	38	39	.02						.02
83.0	86.7	33650	3.7	3.6	2E0	4.77	.19	1.30	1.22	17.11	.10	1	39	40	.07						.01
86.7	90.6	33651	3.9	3.9	2E09	4.44	40.34	.16	.29	10.57	.10	1	37	39	.03						.02
90.6	94.2	33652	3.6	3.4	2D35	3.24	.12	1.50	4.78	31.42	.80	1	14	15	.14						.03
94.2	98.0	33653	3.8	3.7	2E09	4.46	.34	.15	.37	9.95	.10	1	37	39	.01						.03
98.0	101.8	33654	3.8	3.8	2E09	4.16	.23	.14	.68	5.29	1.00	2	33	36	.02						.07
101.8	105.0	33655	3.2	3.2	2E08	4.13	40.24	1.51	1.73	8.40	.10	7	28	35	.03						.26
105.0	110.0	33656	5.0	5.0	2E48	4.36	.25	1.62	3.00	8.09	.10	9	28	37	.02						.22
110.0	115.0	33657	5.0	5.0	2E48	4.02	.35	1.90	3.09	12.13	.10	12	27	39	.07						.28
115.0	120.0	33658	5.0	5.0	2E08	3.68	.48	1.26	.72	34.84	1.00	7	19	27	.62						.19
120.0	125.7	33659	5.7	5.6	2E08	3.59	40.26	.09	1.41	2.80	.10	6	28	34	.11						.10
125.7	128.8	33660	3.1	3.1	2E09	4.45	.35	.04	.47	3.73	.10	1	37	39	.02						.03
128.8	131.7	33661	2.9	2.9	2E1	4.04	.13	.14	.74	5.29	.10	1	31	32	.04						.02
131.7	133.5	33662	1.8	1.7	2E41	3.90	.11	5.96	6.44	21.77	.20	2	23	26	.03						.02
133.5	137.3	33663	3.8	3.8	2E0	3.62	50.12	.28	.44	6.84	.20	2	27	30	.09						.02
137.3	141.0	33664	3.7	3.6	2D39	3.45	.28	3.26	5.11	68.74	2.00	2	15	17	.07						.05
141.0	145.0	33665	4.0	4.0	2C3	3.59	.12	.27	.20	16.48	.40	1	23	25	.03						.01
145.0	150.1	33666	5.1	5.1	2C3	3.48	.11	1.89	1.08	74.03	.40	1	19	21	.04						.05
150.1	154.2	33667	4.1	4.1	2D45	3.42	40.09	3.26	7.82	29.86	.80	1	14	16	.08						.03
154.2	158.0	33668	3.8	3.8	2C3	3.57	.06	.45	.90	7.46	.20		24	24	.06						.01
158.0	162.3	33669	4.3	4.1	2C39	3.91	.20	.18	1.03	2.49	.10	3	27	30							.11
162.3	166.3	33670	4.0	4.0	2E09	3.80	.20	.37	2.04	4.04	.10	6	22	29							.17
166.3	171.3	33671	5.0	5.0	2E49	3.91	40.20	2.19	3.47	4.04	.10	8	20	28	.01						.22
171.3	173.8	33672	2.5	2.5	2E81	4.09	.20	.47	2.13	3.11	.10	8	34	42							.22
173.8	180.0	33673	6.2	5.7	2E81	4.03	.25	.40	1.38	3.42	.10	7	33	40	.02						.18
180.0	185.0	33674	5.0	4.9	2E89	4.20	.61	.09	1.12	2.49	.10	10	25	35							.27
185.0	190.0	33675	5.0	5.0	2E89	4.41	40.31	.15	2.01	4.04	.10	11	26	38							.33
190.0	195.0	33676	5.0	5.0	2E19	4.08	.53	.67	.58	9.64	.10	4	26	31	.01						.15
195.0	200.0	33677	5.0	5.0	2E89	4.37	.78	1.01	2.31	10.88	.10	9	36	45							.30
200.0	205.0	33678	5.0	4.8	2E89	4.02	.66	1.00	.99	20.22	.30	3	27	30	.01						.09
205.0	209.0	33679	4.0	4.0	2E89	4.47	40.39	.10	.98	10.57	.10	6	31	38	.01						.22
209.0	215.0	33680	6.0	5.8	2E09	4.25	.58	.14	.95	14.62	.10	1	33	34	.02						.04
215.0	220.0	33681	5.0	5.0	2E09	4.44	.52	.88	2.22	14.00	.10	2	31	34	.01						.07
220.0	225.0	33682	5.0	5.0	2E08	4.26	40.17	.15	1.49	7.15	.10	2	32	34	.01						.07
225.0	230.0	33683	5.0	5.0	2E08	4.27	.17	.14	1.98	6.22	.10	2	31	33	.01						.08
230.0	235.0	33684	5.0	5.0	2C3	4.07	.08	1.18	3.95	10.89	.10	1	28	30	.01						.04
235.0	239.0	33685	4.0	4.0	2C3	3.96	40.04	.77	1.96	8.71	.10	1	28	29	.03						.03
239.0	243.2	33686	4.2	4.1	2C3	3.96	.04	1.07	.56	8.09	.10		29	29	.03						.02
243.2	248.0	33687	4.8	4.8	2D43	3.49	50.06	3.42	8.23	23.02	.10	2	17	20	.06						.03
248.0	252.0	33688	4.0	3.7	2D43	3.57	50.05	3.58	10.79	26.13	.10	2	17	20	.04						.03
252.0	255.3	33689	3.3	3.2	2E4	4.49	.03	3.00	6.55	25.50	.10	1	32	33	.01						.03
255.3	258.0	33690	2.7	2.7	2D0	3.13	.12	1.48	2.63	15.86	.10	6	6	12	.23						.03
258.0	261.7	33691	3.7	3.4	2C0	2.93	.17	.26	.25	5.91	.20	3	5	9	.28						.02

DDH: 84F-05

---DEPTHS---		SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	---ASSAYS---					S.G. W.R.			
FROM	TO											Po %	Py %	TOT Fe	BAO %	Hg %		Mn %	As %	Ba %
261.7	265.0	33692	3.3	3.0	2D5	2.95	.08	1.52	3.73	18.04	.30	2	4	6	.30	.03				
265.0	271.3	33693	6.3	6.3	2C35	3.29	21.07	.74	2.16	18.04	.30	2	14	16	.14	.02				
271.3	275.0	33694	7.7	7.7	2C3	3.36	.05	.94	2.40	19.28	.40	2	15	17	.14	.02				
275.0	279.0	33695	4.0	4.0	2D3	3.14	.07	1.10	2.95	23.33	.30	3	7	11	.17	.03				
279.0	283.0	33696	4.0	4.0	2D0	2.96	.08	1.45	3.42	18.66	.30	4	4	8	.21	.04				
283.0	285.9	33697	2.9	2.8	2D0	2.99	21.07	1.41	3.08	22.39	.30	3	5	9	.17	.04				
285.9	289.0	33698	3.1	3.1	2A13	3.14	.05	1.02	2.76	23.95	.30	1	11	13	.17	.02				
289.0	294.0	33699	5.0	4.6	2A13	3.03	.05	.28	.64	12.75	.30	1	9	11	.20	.02				
294.0	299.0	33700	5.0	4.6	2C0&	3.07	.07	.96	1.14	21.77	.10	3	8	11	.30	.03				
299.0	305.2	33701	6.2	6.2	2C0&	3.00		.74	1.82	18.35	.10	3	5	8	.23	.03				
305.2	309.0	33702	3.8	3.8	2D5	2.85	21.07	1.56	3.80	20.22	.50	1	2	4	.25	.02				
309.0	314.0	33703	5.0	5.0	2A13	2.96	.06	.50	1.61	15.55	.10	1	6	8	.23	.02				
314.0	319.0	33704	5.0	5.0	2A13	3.00	.07	.16	.10	9.02	.10	3	7	11	.21	.02				
319.0	324.2	33705	5.2	5.2	2A13	2.97	.16	.13	.05	12.13	.10	5	7	12	.18	.02				
324.2	330.4	33706	6.2	6.2	2C7	3.13	21.19	.58	.35	20.84	.10	11	6	17	.13	.02				
330.4	333.0	33707	2.6	2.5	2A13	2.97	.05	1.31	.05	13.37	.50	2	7	9	.21	.02				
333.0	336.0	33708	3.0	3.0	2A13	2.92	.05	.30	1.53	28.62	.30	2	9	11	.22	.02				
336.0	339.9	33709	3.9	3.9	2A13	2.87	.05	.22	1.88	9.02	.10	4	3	7	.20	.02				
339.9	344.5	33710	4.6	4.5	2C7	3.02	21.15	.28	.87	19.60	.10	11	1	13	.18	.02				
344.5	349.0	33711	4.5	4.5	2C7	3.19	.19	.49	.28	12.44	.10	14	3	17	.17	.02				
349.0	353.3	33712	4.3	3.3	2C79	3.04	.22	.77	.12	15.55	.10	11		11	.13	.02				
353.3	359.0	33713	5.7	5.7	2C7&	2.98	.11	.22	.06	5.91	.10	11		11	.20	.02				
359.0	364.0	33714	5.0	5.0	2C7&	3.02	21.16	.14	.04	4.98	.10	9	3	12	.18	.03				
364.0	369.6	33715	5.6	5.5	2C79	3.39	.29	.38	.23	10.57	.10	21		22	.13	.03				
369.6	372.8	33716	3.2	3.2	2C79	3.33	.29	.30	.58	10.57	.10	14	5	19	.16	.03				
372.8	376.0	33717	3.2	3.2	2D0	3.48	.16	3.83	4.65	60.03	.30	8	4	12	.13	.04				
376.0	378.5	33718	2.5	2.5	2D4	3.37	21.13	6.90	8.81	102.95	.50	7	3	10	.06	.05				
378.5	383.3	33719	4.8	4.5	2L2	3.13	Waste .08	2.72	.46	63.45	.10	6	2	8	.18	.04				
383.3	386.8	33720	3.5	3.5	2L2	2.85	.11	.23	.09	5.29	.10	6	4	10	.24	.04				
386.8	391.8	33721	5.0	5.0	2A1	2.84	.06	1.04	1.72	15.86	.10	3	2	5	.18	.04				
391.8	396.7	33722	4.9	4.8	2A14	2.82	.04	1.18	3.95	13.37	.10	3	2	5	.20	.04				
396.7	399.7	33723	3.0	2.7	0Q9	3.04	21.12	12.65	.98	286.16	.80	3	2	6	.06	.04				
399.7	403.0	33724	3.3	3.3	2B09	3.05	.20	1.79	.58	39.81	.30	4	4	8	.11	.03				
403.0	407.0	33725	4.0	3.9	2D0&	2.80	.11	2.41	4.11	29.24	.10	4	3	7	.08	.03				
407.0	411.2	33726	4.2	4.2	2L2	2.89	Waste .06	1.11	2.14	13.68	.10	2	1	3	.16	.07				
411.2	414.5	33727	3.3	3.3	2B4&	2.94	21.08	2.17	2.82	26.75	.10	3	2	5	.10	.06				
414.5	417.0	33728	2.5	2.5	2B0&	2.82	.05	1.15	1.26	17.73	.10	3	1	5	.11	.05				

DDH: 84F-07

-----DEPTHS-----				-----ASSAYS-----																
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
563.8	566.3	33636	2.5	2.5	2E49	3.89	.22	5.00	8.61	83.98	.20	9	16	25	.11		.16			
566.3	570.3	33637	4.0	4.0	2D0	3.04	.10	1.62	3.97	33.90	.10	4	5	10	.06		.07			
570.3	574.2	33638	3.9	3.9	2D0	3.14	.11	1.37	4.67	28.30	.10	6	7	13	.09		.07			
574.2	579.2	33639	5.0	4.7	2A0	2.85	.08	1.55	3.85	36.08	.20	3	3	7	.24		.04			
579.2	583.3	33640	4.1	4.0	2A0	2.85	.05	.80	1.86	20.53	.10	3	2	5	.21		.06			

DDH: 84F-08

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													S.G. W.R.
FROM	TO						CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	
43.2	49.2	33604	6.0	6.0	2C39	3.53	.21	.90	1.21	31.10		.60	5	18	23	.08		.06		
49.2	54.7	33605	5.5	5.5	2D3	3.69	.07	1.28	3.48	19.60		.40	1	22	24	.06		.01		
54.7	56.8	33606	2.1	2.1	2D43	3.51	40 .12	4.13	9.84	35.77		.20	6	10	17	.08		.10		
56.8	61.5	33607	4.7	4.7	2C37	3.18	.35	.80	1.53	13.37		.10	12	7	19	.07		.09		
90.2	92.5	33608	2.3	2.3	2E19	3.66	.23	.12	.51	7.78		.10	3	23	27	.02		.03		
92.5	97.5	33609	5.0	5.0	2D3	3.36	.14	1.57	4.17	17.73		.10	3	14	18	.07		.03		
97.5	102.5	33610	5.0	5.0	2D3	3.19	21 .11	2.68	5.57	23.02		.10	3	11	15	.06		.03		
102.5	107.5	33611	5.0	5.0	2A43	3.36	.06	5.19	8.62	46.97		.40	2	13	15	.08		.01		
107.5	112.5	33612	5.0	4.6	2A43	3.33	.07	2.61	5.86	29.24		.20	2	14	16	.07		.02		
112.5	117.5	33613	5.0	4.7	2A43	3.35	.07	2.95	7.56	34.52		.40	1	14	16	.06		.01		
117.5	122.5	33614	5.0	5.0	2A43	3.60	21 .05	1.66	5.43	23.33		.10	1	19	21	.09		.01		
122.5	128.3	33615	5.8	5.3	2A43	3.38	.05	1.85	5.44	21.46		.10	2	14	16	.11		.01		
128.3	131.2	33616	2.9	2.9	2D35	3.46	.03	2.40	7.09	26.75		.20	1	15	17	.10		.01		
131.2	137.6	33617	6.4	6.4	2A43	3.37	.04	2.48	5.73	27.68		.40	1	15	17	.09		.01		
137.6	140.7	33618	3.1	3.1	2A3	3.15	21 .05	.53	2.15	11.20		.10	1	15	16	.13		.01		
140.7	146.7	33619	6.0	6.0	2D35	3.34	.08	1.11	3.29	17.11		.10	2	18	21	.09		.02		
146.7	152.0	33620	5.3	5.3	2D35	3.22	.08	.93	4.57	19.28		.10	4	11	15	.15		.02		
152.0	157.0	33621	5.0	5.0	2A13	3.01	.06	.23	.61	14.93		.10	4	11	15	.11		.04		
157.0	162.0	33622	5.0	5.0	2A41	3.36	21 .06	1.42	3.63	27.06		.20	2	14	16	.08		.02		
162.0	168.1	33623	6.1	6.1	2A41	3.27	.05	1.69	4.89	27.68		.10	2	13	15	.11		.02		
168.1	172.0	33624	3.9	3.7	2A13	3.07	.08	.29	.31	14.00		.10	5	9	14	.15		.01		
172.0	175.2	33625	3.2	3.2	2A13	3.09	.04	.33	1.54	13.37		.10	1	13	14	.13		.01		
175.2	180.2	33626	5.0	5.0	2C0	3.29	21 .13	.52	1.14	13.06		.10	5	12	17	.05		.02		
180.2	185.6	33627	5.4	5.4	2C0	3.51	.11	.24	1.76	9.95		.10	9	13	22	.11		.01		
185.6	190.2	33628	4.6	4.6	2C5	3.56	.06	.30	1.40	11.82		.20	7	18	25	.10		.01		
190.2	195.2	33629	5.0	5.0	2A13	3.04	21 .08	.40	1.37	13.06		.10	3	10	14	.20		.01		
195.2	200.2	33630	5.0	5.0	2A13	3.18	.07	.67	1.05	18.35		.20	3	14	18	.11		.01		
200.2	204.6	33631	4.4	4.4	2A13	3.16	.09	.24	1.71	12.13		.20	5	13	18	.16		.01		
204.6	209.0	33634	4.4	4.4	2H9	4.10	21 .33	1.08	4.90	24.26		.10	35	3	39	.01		.02		
209.0	214.1	33635	5.1	5.1	2D09	3.09	.21	1.51	3.93	27.37		.20	6	5	12	.16		.02		

DDH: 84F-09

-----DEPTHS-----							-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %	S.G. W.R.	
747.1	751.0	33772	3.9	3.8	2D4	3.36	.13	5.14	9.20	116.64		.40	7	7	14	.09		.12				
751.0	753.9	33773	2.9	2.9	2A1	2.79	.15	.39	.87	9.33		.10	4	4	8	.21		.04				
753.9	756.3	33774	2.4	2.4	2D09	3.37	.22	2.94	5.83	50.70		.30	7	11	18	.08		.10				
756.3	759.6	33775	3.3	3.3	2D0	2.89	2.09	4.08	3.41	74.96		.30	3	3	6	.22		.05				
759.6	763.0	33776	3.4	3.4	2B0	2.69	.06	.76	1.67	16.48		.10	2	1	3	.30		.03				
763.0	767.7	33777	4.7	4.7	2A41	2.99	.08	5.22	3.69	110.73		.50	2	2	5	.24		.05				
767.7	772.5	33778	4.8	4.8	2A41	2.74	.05	1.15	2.86	21.15		.10	2	1	3	.15		.04				

DDH: 84F-10

-----DEPTHS-----				-----ASSAYS-----																
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
400.9	403.0	33779	2.1	2D49	3.18	.38	4.47	6.80	60.96						.10		.12			
403.0	405.8	33780	2.8	2G48	4.62	.49	4.54	5.40	67.50						4.15		.29			
405.8	409.5	33781	3.7	2F49	4.72	.22	4.68	5.97	64.07						.10		.19			
409.5	412.7	33782	3.2	2G4	4.35	.18	5.16	5.92	82.11						6.88		.27			
412.7	415.9	33783	3.2	2G4	4.61	.11	4.80	5.10	93.93						4.41		.32			
415.9	417.3	33784	1.4	2G47	4.37	.22	5.01	5.99	87.71						5.14		.26			
417.3	422.0	33785	4.7	2D0	3.11	.11	1.42	4.49	25.19						.20		.06			
422.0	426.7	33786	4.7	2D0	2.95	.08	1.85	4.53	30.17						.11		.06			
426.7	430.9	33787	4.2	2A1&	2.88	.05	.78	1.80	15.55						.30		.03			
430.9	435.1	33788	4.2	2A1&	2.91	.06	1.24	2.28	23.64						.29		.04			
435.1	438.5	33789	3.4	2B5	2.88	.08	.88	1.86	25.82						.22		.04			
438.5	442.0	33790	3.5	2D5	3.00	.08	1.85	3.48	33.59						.23		.04			
442.0	447.2	33791	5.2	2A41	3.12	.09	3.27	4.03	69.98						.20		.09			
447.2	451.5	33792	4.3	2A0	2.75	.05	.64	1.72	12.44						.54		.03			
451.5	454.8	33793	3.3	2B5	2.82	.07	.97	2.00	19.91						.36		.03			
454.8	458.2	33794	3.4	2B45	2.98	.07	3.96	2.07	90.51						.31		.04			
458.2	463.9	33795	5.7	2A03	2.89	.10	1.97	1.13	27.99						.17		.12			
463.9	469.5	33796	5.6	2A03	2.79	.05	.13	.22	2.49						.40		.16			
469.5	475.2	33797	5.7	2A03	2.84	.10	.64	.41	43.55						.36		.10			

16A
0.26, 4.27, 5.80, 35.62

DDH: 84F-13

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													S.G. W.R.
FROM	TO						CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	
71.1	74.4	33810	3.3	3.3	2D0	3.21	.18	1.10	4.51	19.91	.26	3	8	12	.31		.05			
74.4	79.9	33811	5.5	5.3	2D0	3.63	.14	4.09	5.33	62.83	.11	6	13	20	.34		.19			
79.9	84.6	33812	4.7	4.6	2A1	2.91	.07	.98	1.71	21.15	.03	2	3	5	.69		.03			
84.6	89.6	33813	5.0	5.0	2D3&	3.17	.08	2.02	5.63	44.48	.04	4	4	8	.18		.04			
89.6	95.0	33814	5.4	5.4	2A41	3.09	.08	1.13	5.07	23.33	.07	4	4	8	.37		.03			
95.0	99.3	33815	4.3	4.1	2A41	2.90	.05	.83	2.97	18.66	.11	3	2	5	.51		.03			
99.3	104.3	33816	5.0	5.0	2A0	2.86	.04	1.26	2.67	22.71	.13	2	1	4	.82		.03			
104.3	108.0	33817	3.7	3.7	2B0	2.73	.05	.38	1.00	9.33	.03	2	2	4	.79		.02			
108.0	110.4	33818	2.4	2.4	2B0	2.80	.07	.43	.84	12.75	.13	2	3	5	.68		.02			
110.4	115.4	33819	5.0	2.2	2B0	2.80	.06	.75	2.27	18.35	.08	2	3	5	.63		.02			
115.4	120.4	33820	5.0	2.7	2D0	3.00	.09	1.51	5.39	27.68	.07	5	5	10	.30		.05			
120.4	124.9	33821	4.5	4.5	2D0	2.80	.08	2.12	3.56	41.06	.05	3	2	6	.43		.04			
124.9	129.0	33822	4.1	4.0	1E19	2.60	.05	.49	1.29	10.58	.05	2	2	4	.57		.10			
174.1	179.7	33823	5.6	5.5	0Q9	3.17	.32	2.68	4.79	93.62	.07	7	7	14	.15		.06			
179.7	183.5	33824	3.8	3.4	2L14	2.80	.28	.97	2.36	47.28	.50	6	1	7	.27		.05			

DDH: 84F-14

-----DEPTHS-----				-----ASSAYS-----																	
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %	S.G. W.R.	
228.5	231.5	33825	3.0	2.8	2A1	3.24	21.18	1.44	3.14	37.32		.05	8	8	17	.42		.05			

DDH: 84F-17

---DEPTH---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													S.G. W.R.
FROM	TO						CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	
127.0	130.0	33798	3.0	3.0	2A0	3.17	.19	.34	.38	12.44		.25	2	10	13	.64		.03		
130.0	133.4	33799	3.4	3.4	2A33	3.35	.50	.30	.28	19.91		.42	4	15	20	.22		.04		
133.4	137.0	33800	3.6	3.6	2D0	3.40	.18	.42	5.17	13.06		.45	3	11	14	.29		.04		
137.0	139.7	33801	2.7	2.7	2D4	3.44	.10	4.13	12.60	40.44		.43	3	9	12	.31		.03		
139.7	141.6	33802	1.9	1.9	2F43	4.05	.12	5.50	6.94	85.22		.21	7	18	26	1.04		.25		
141.6	146.5	33803	4.9	4.9	2D0&	2.92	.08	1.70	2.90	24.26		.08	2	2	5	.17		.06		
146.5	153.1	33804	6.6	6.6	2D0&	2.86	.04	1.71	2.68	26.13		.03	3	2	5	.41		.06		
153.1	154.4	33805	1.3	1.3	2Q9	3.81	.21	5.93	8.35	101.09		.05	7	12	20	.33		.14		
154.4	160.7	33806	6.3	6.0	2B0	2.94	.07	.58	1.23	11.51		.02	3	3	6	4.34		.03		
160.7	164.7	33807	4.0	4.0	2E43	3.91	.21	3.13	7.39	58.16		.05	10	14	25	2.39		.12		
164.7	170.8	33808	6.1	4.1	2C0	3.08	.09	.99	2.31	23.02		.03	4	5	10	.66		.04		
170.8	175.2	33809	4.4	4.2	2A0	2.83	.03	.52	.92	9.33		.02	2	1	3	.91		.03		

DDH: 84F-18

Include
waste
10E

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	---ASSAYS---										S.G. W.R.
FROM	TO												Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %			
379.9	383.2	33826	3.3	3.3	2D39	3.33	.57	.61	.18	21.27		.31	6	13	20	.22						.04	
383.2	386.0	33827	2.8	2.6	2D39	3.17	.26	2.00	5.83	41.68		1.20	5	6	12	.18						.05	
386.0	389.6	33828	3.6	3.5	2D39	3.41	.39	1.54	8.85	29.55		.45	13	4	17	.63						.15	
389.6	391.0	33829	1.4	1.4	2H41	4.13	.50	4.75	7.46	74.03		.19	24	7	31	.30						.32	
391.0	396.0	33830	5.0	5.0	2E46	4.68	.05	4.61	6.79	64.07		.20	2	28	31	3.09						.29	
396.0	400.0	33831	4.0	4.0	2G4	4.64	.16	4.63	5.64	55.37		.22	2	23	26	8.55						.27	
400.0	405.4	33832	5.4	5.4	2G4	4.65	.14	5.24	6.07	90.82		.27	7	18	25	11.48						.37	
405.4	409.5	33833	4.1	4.1	2H49	4.30	.30	5.11	7.46	65.63		.09	20	10	30	.54						.27	
420.4	424.0	33834	3.6	3.6	2H43	4.28	.29	5.62	8.42	71.85		.07	18	11	30	.70						.20	
424.0	426.9	33835	2.9	2.9	2H43	4.44	.28	6.03	7.34	91.45		.08	14	17	32	.76						.20	
426.9	432.0	33836	5.1	5.0	2H43	4.45	.31	5.03	6.69	76.20		.13	35	1	37	2.31						.19	
432.0	437.0	33837	5.0	5.0	2H43	4.41	.31	5.96	7.62	93.31		.06	23	9	33	2.32						.20	
437.0	441.0	33838	4.0	4.0	2K43	4.20	.27	4.09	5.15	59.41		.05	17	14	32	.26						.14	
441.0	444.0	33839	3.0	3.0	2K43	4.16	.29	4.53	6.18	65.32		.05	17	12	30	.20						.12	
444.0	447.8	33840	3.8	3.6	2H43	4.39	.30	5.96	9.11	86.16		.06	25	5	30	.28						.11	
447.8	450.5	33841	2.7	2.7	2G4	4.59	.11	4.18	5.81	59.72		.05	5	19	24	13.49						.08	
450.5	453.6	33842	3.1	3.1	2G4	4.68	.14	4.19	5.98	40.12		.04	1	18	20	20.69						.05	
453.6	457.4	33843	3.8	3.8	2E09	4.89	.31	1.35	.76	16.49		.03	1	36	37	.52						.02	
457.4	461.0	33844	3.6	3.6	2E46	4.74	.46	3.27	4.93	32.35		.04	1	25	27	10.07						.03	
461.0	464.8	33845	3.8	3.6	2E46	4.73	.22	2.11	3.19	143.08		.05	2	31	33	3.54						.03	
464.8	468.0	33846	3.2	3.2	2G49	4.73	.20	5.95	7.28	51.94		.04	2	21	23	10.46						.05	
468.0	471.5	33847	3.5	3.5	2G4	4.71	.13	4.84	7.12	56.30		.08	2	12	14	26.72						.06	
471.5	477.2	33848	5.7	5.7	2E46	4.71	.24	3.01	3.32	33.28		.04	3	30	34	1.15						.06	
477.2	483.3	33849	6.1	6.1	2E49	4.65	.23	2.74	4.90	30.48		.05	3	30	33	.29						.08	
483.3	488.3	33850	5.0	5.0	2E09	4.52	.54	1.72	1.69	42.30		.15	5	30	35	.17						.20	
488.3	492.6	33851	4.3	3.7	2E09	4.59	.90	1.53	1.27	35.46		.10	3	23	27	.15						.17	
492.6	495.0	33852	2.4	2.4	2E09	4.49	.26	1.84	1.90	25.82		.06	4	25	30	.15						.19	
495.0	501.0	33853	6.0	6.0	2E4	4.55	.19	4.19	6.12	37.01		.03	3	28	31	.15						.05	
501.0	506.4	33854	5.4	5.4	2E4	4.76	.09	4.96	9.70	39.19		.03	2	28	30	.15						.02	
506.4	512.0	33855	5.6	5.6	2E49	4.79	.37	3.07	4.43	32.97		.03	2	32	34	.15						.04	
512.0	517.0	33856	5.0	4.7	2E4	4.80	.18	2.15	4.58	34.53		.05	4	31	35	.16						.04	
517.0	520.4	33857	3.4	3.4	2E4	4.81	.11	2.32	4.81	28.30		.10	3	32	35	.15						.06	
520.4	523.1	33858	2.7	2.6	2D09	3.21	.27	2.81	4.01	62.21		.09	4	7	11	.30						.03	
523.1	528.4	33859	5.3	5.1	2D39	3.13	.21	1.37	2.83	28.93		.07	4	8	12	.35						.03	
528.4	533.5	33860	5.1	5.1	2D39	3.02	.13	1.44	5.22	37.32		.21	4	6	10	.31						.03	
533.5	539.4	33861	5.9	5.9	2A0	2.81	.27	1.15	2.05	33.28		.11	3	2	5	.26						.04	

DDH: 84F-19

DEPTHS		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	ASSAYS													
FROM	TO						CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe %	BAO %	Hg %	Mn %	As %	Ba %
339.3	340.4	33862	1.1	1.1	1E19	2.75 <i>60</i>	.07	.11	.18	6.84			.05	3	2	5	.50		.04	
340.4	345.5	33863	5.1	5.0	2E19	3.48	.41	.09	.26	14.62			.14	6	16	23	.21		.09	
345.5	348.6	33864	3.1	3.1	2D43	3.58	.09	1.95	14.10	35.77			.15	4	12	17	.24		.10	
348.6	351.6	33865	3.0	3.0	2H46	4.35	.28	4.55	7.04	76.83			.13	18	11	30	5.73		.23	
351.6	357.4	33866	5.8	5.8	2H46	4.14	.28	4.90	8.79	81.18			.11	21	8	30	3.00		.29	
357.4	359.9	33867	2.5	2.5	2G07	4.40	.25	3.09	5.40	57.54			.07	24	2	27	18.47		.15	
359.9	362.0	33868	2.1	2.0	2H69	4.30	.32	3.36	6.24	67.81			.13	39		39	1.19		.20	
362.0	366.6	33869	4.6	4.4	2L14	3.30	.40	3.35	3.27	68.12			.05	8	6	15	3.85		.14	
366.6	370.8	33870	4.2	4.2	2L14	2.77	.04	.32	.46	11.82			.11	4	3	8	3.24		.07	
370.8	375.8	33871	5.0	5.0	2L14	2.73	.04	.12	.27	7.78			.10	4	3	7	2.25		.06	
375.8	378.5	33872	2.7	2.7	2E41	3.86	.09	3.58	9.08	57.85			.07	7	16	23	2.64		.13	
378.5	380.8	33873	2.3	2.3	2H43	4.38	.25	5.82	9.97	86.16			.08	27	9	36	.30		.12	
380.8	384.0	33874	3.2	3.0	2G47	4.34	.16	4.50	8.98	59.41			.10	13	9	22	21.12		.10	
384.0	386.2	33875	2.2	2.2	2K47	3.99	.19	7.52	12.00	103.58			.09	15	12	27	1.47		.15	
386.2	390.0	33876	3.8	3.8	2L14	2.98	.07	.73	.97	13.69			.06	4	4	9	5.61		.04	
390.0	391.8	33877	1.8	1.8	2Q96	3.90	.13	4.62	8.80	99.53			.09	10	16	26	2.94		.21	
391.8	393.9	33878	2.1	2.1	2H06	2.96	.12	.87	1.12	17.11			.02	4	3	7	4.41		.03	
393.9	398.6	33879	4.7	4.7	2H49	4.14	.31	5.33	7.78	98.60			.07	29	9	38	1.03		.30	
398.6	400.0	33880	1.4	1.4	1H4	2.92	.14	1.12	1.95	18.97			.03	9	6	15	3.39		.18	
400.0	402.0	33881	2.0	2.0	2E4*	4.26	.20	7.33	9.39	129.08			.09	12	14	27	5.36		.39	
402.0	403.0	33882	1.0	1.0	1H4	2.91	.08	1.54	1.04	21.15			.03	10		11	2.56		.15	
403.0	406.5	33883	3.5	3.5	2E46	4.09	.25	4.47	12.00	85.23			.09	15	12	28	4.05		.40	
406.5	408.4	33884	1.9	1.8	2L14	3.07	.18	.51	.57	14.00			.03	14	2	16	5.21		.14	
408.4	409.2	33885	.8	.8	2E36	3.74	.36	1.87	1.53	45.41			.17	8	21	30	2.92		.21	
409.2	410.5	33886	1.3	1.3	2B06	2.87	1.04	.57	.99	39.19			.66	2	4	7	4.16		.09	
410.5	412.7	33887	2.2	2.2	2E46	4.11	.26	3.70	2.81	81.18			.10	8	24	32	1.16		.31	
412.7	414.7	33888	2.0	1.6	1H4	2.85	.12	1.42	.40	41.06			1.65	8	4	13	3.07		.10	
414.7	421.0	33889	6.3	6.3	1H4	2.99	.24	1.43	.35	50.08			1.17	7	5	13	3.75		.14	
421.0	422.8	33890	1.8	1.8	2E46	4.02	.27	1.77	2.32	45.72			.22	8	24	33	2.40		.22	
422.8	425.8	33891	3.0	2.3	2D63	3.69	.15	.77	2.12	32.04			.62	4	16	21	11.08		.13	
425.8	429.3	33892	3.5	3.5	2G4	4.46	.07	5.25	9.03	93.00			.25	2	3	6	26.53		.09	
429.3	433.8	33893	4.5	4.5	2G4	4.47	.29	4.45	4.79	73.72			.25	5	3	9	7.41		.12	
433.8	438.8	33894	5.0	5.0	2E0&	4.56	.11	.96	.92	17.11			.10	1	35	37	.26		.06	
438.8	443.8	33895	5.0	5.0	2E0&	4.62	.23	2.14	1.53	37.32			.06	1	36	38	.16		.06	
443.8	447.0	33896	3.2	3.2	2E0&	4.55	.18	2.18	1.48	34.53			.07		35	36	.31		.01	
447.0	452.0	33897	5.0	5.0	2E1	3.96	.04	.42	.23	9.95			.08		29	29	.61		.01	
452.0	456.2	33898	4.2	4.2	2E1	4.30	.09	1.86	2.95	27.99			.09	2	24	27	3.54		.04	
456.2	461.2	33899	5.0	5.0	2D0&	3.30	.25	4.54	3.44	51.63			.08	6	7	14	.72		.05	
461.2	467.4	33900	6.2	6.1	2D0&	3.03	.27	1.37	3.31	24.57			.15	6	5	11	.50		.05	
467.4	469.1	33901	1.7	1.7	1H4	2.91	.58	.94	1.90	92.07			3.33	4	4	8	.47		.06	
469.1	474.0	33902	4.9	4.9	2D09	3.03	.27	1.15	3.44	68.12			.54	5	5	11	.58		.05	
474.0	478.0	33903	4.0	4.0	2E48	4.56	.20	1.72	3.02	20.84			.12	4	29	33	.17		.11	
478.0	481.3	33904	3.3	3.3	2E48	4.66	.29	1.73	2.83	10.89			.05	7	26	34	.14		.22	
481.3	485.5	33905	4.2	4.2	2E4	4.60	.13	1.99	5.69	9.95			.07	3	28	31	.36		.06	
485.5	489.8	33906	4.3	4.3	2G49	4.46	.24	3.99	9.08	21.15			.05	4	19	23	9.26		.16	
489.8	494.6	33907	4.8	4.8	2E49	4.43	.25	3.01	6.21	18.97			.03	5	24	30	.41		.17	
494.6	501.1	33908	6.5	6.5	2E49	4.53	.22	5.65	6.57	36.08			.03	5	22	27	1.12		.14	
501.1	505.0	33909	3.9	3.9	2G48	4.57	.18	6.33	10.39	59.10			.05	5	16	21	10.71		.22	
505.0	509.8	33910	4.8	4.8	2E4	4.58	.26	3.76	5.17	35.46			.04	5	23	28	5.68		.19	
509.8	514.8	33911	5.0	5.0	2E49	4.46	.30	2.11	3.93	22.40			.04	7	24	32	.29		.23	
514.8	519.8	33912	5.0	5.0	2E49	4.38	.31	1.89	3.20	17.11			.03	8	23	32	.17		.24	

DDH: 84F-19

-----DEPTHS-----				-----ASSAYS-----																	
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %	S.G. W.R.	
519.8	524.8	33913	5.0	5.0	2E8&	4.45	.19	1.18	2.80		12.75			.03	10	23	33		.15		.25
524.8	529.0	33914	4.2	4.2	2E48	4.69	50.19	4.13	5.93		49.46			.03	6	24	30		.16		.25
529.0	534.0	33915	5.0	4.0	2E4	4.50	.10	5.13	6.21		66.87			.04	4	22	27		.18		.17
534.0	539.0	33916	5.0	4.9	2E4	4.51	.17	2.10	4.27		27.06			.03	4	27	31		.23		.06
539.0	544.0	33917	5.0	4.9	2E4	4.51	50.40	2.20	3.97		24.57			.04	7	25	32		.17		.07
544.0	548.0	33918	4.0	3.8	2E4	4.88	.06	4.08	6.16		20.53			.03	1	28	30		.15		.03
548.0	552.4	33919	4.4	4.4	2E4	4.73	.07	3.00	5.74		16.80			.06	1	28	30		.16		.02
552.4	553.1	33920	.7	.7	1H4	3.29	50.12	1.42	1.94		11.20			.03	4	13	17		.44		.06
553.1	558.7	33921	5.6	5.6	2E4	4.71	.19	2.74	5.39		20.53			.04	3	28	31		.16		.03
558.7	561.7	33922	3.0	3.0	2D0	3.19	.13	1.95	4.44		21.46			.03	5	7	12		.28		.07
561.7	565.8	33923	4.1	4.1	2D0	2.91	.08	1.64	4.40		25.19			.06	4	2	6		.30		.05
565.8	566.7	33924	.9	.9	2C0	2.88	21.10	.30	.40		7.15			.02	3	2	6		.36		.04
566.7	572.0	33925	5.3	5.3	0Q0&	2.72	.11	.83	.35		38.26			.02	1		1		.21		.02
572.0	578.9	33926	6.9	6.5	0Q0&	2.84	.32	1.31	.48		141.52			.02	5		5		.17		.06

DDH: 84F-20

---DEPTHS---								-----ASSAYS-----													
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
348.8	350.3	33944	1.5	1.5	2C9	2.88	.64	.30	.48	27.06		.05	4	4	8	.42					.11
350.3	351.9	33945	1.6	1.6	2E49	3.90	³³ .22	3.79	4.67	73.41		.04		23	24	.22					.12
351.9	355.0	33946	3.1	2.9	2E0	4.22	.05	1.02	1.27	17.42		.07	1	29	31	.45					.01
355.0	356.7	33947	1.7	1.7	2G02	4.55	.10	2.53	3.72	32.97		.18	2	31	33	9.96					.03
356.7	359.1	33948	2.4	2.4	2G4	4.61	.13	6.44	8.19	90.82		.06	1	19	20	10.43					.12
359.1	362.1	33949	3.0	3.0	2G4	4.73	⁶⁰ .12	6.75	8.84	94.25		.09	4	18	22	15.14					.07
362.1	367.0	33950	4.9	4.5	2E4&	4.71	.17	7.22	7.97	139.03		.03	4	19	23	.50					.29
367.0	368.2	33951	1.2	1.2	2E49	3.51	³³ .33	4.28	.57	87.09		.05		22	22	.37					.01
368.2	371.4	33952	3.2	3.0	2E46	4.59	.04	4.04	7.98	55.05		.03	1	33	34	2.95					.01
371.4	375.4	33953	4.0	3.9	2D43	3.32	.09	4.14	8.40	58.48		.17		19	20	.22					.01
375.4	379.5	33954	4.1	4.1	2D3	3.71	⁶⁰ .07	1.29	3.08	16.80		1.37	2	26	28	.20					.12
379.5	384.5	33955	5.0	5.0	2E4	4.78	.07	2.58	5.38	28.63		.04	1	15	17	.17					.05
384.5	385.3	33956	.8	.8	2G1	4.62	.03	.60	.95	10.57		.07		28	29	6.32					.01
385.3	389.3	33957	4.0	3.9	2E41	3.46	.04	1.72	3.19	28.30		.12		26	27	.18					.01
389.3	393.0	33958	3.7	3.2	2E1	4.17	.04	.40	.64	12.75		.19	1	28	29	.17					.01
393.0	397.0	33959	4.0	3.7	2E4	4.61	⁵⁰ .07	5.32	7.22	85.23		.32	1	24	26	.15					.02
397.0	399.1	33960	2.1	2.1	2E1	3.96	.16	3.78	3.72	22.71		.04	1	36	37	.21					.02
399.1	402.3	33961	3.2	3.0	2E09	4.60	.27	1.11	.98	5.60		.04	1	37	38	.14					.03
402.3	405.5	33962	3.2	2.0	2E09	4.71	.34	.60	3.46	3.01		.02	1	31	33	.14					.03
405.5	407.3	33963	1.8	1.8	2C39	4.16	.29	.12	1.75	7.47		.08	1	23	24	.17					.02
407.3	409.1	33964	1.8	1.8	2C35	3.82	.10	.59	3.29	7.78		.10	1	27	28	.18					.02
409.1	414.0	33965	4.9	4.9	2C3&	4.03	.11	.53	1.59	6.22		.07	1	27	29	.15					.02
414.0	418.9	33966	4.9	4.9	2C3&	4.18	⁴⁰ .25	.06	1.22	11.51		.08	1	29	31	.15					.02
418.9	423.8	33967	4.9	4.9	2C3&	4.13	.08	.17	.84	4.67		.08	1	18	19	.15					.02
423.8	424.7	33968	.9	.9	2D39	3.50	.22	.36	4.85	8.71		.11	2	16	19	.27					.05
424.7	425.7	33969	1.0	1.0	2C3	3.71	.13	.11	2.30	4.98		.10	1	23	25	.20					.02
425.7	426.9	33970	1.2	1.2	2C53	3.58	.04	.16	1.24	3.42		.12		23	24	.20					.02
426.9	428.7	33971	1.8	1.2	2D43	3.77	⁴⁰ .20	8.34	6.25	55.37		.13	2	15	17	.22					.03
428.7	432.8	33972	4.1	4.1	2C39	4.22	.26	.58	1.46	12.13		.10	1	31	33	.14					.02
432.8	436.9	33973	4.1	4.0	2C39	3.86	.43	.83	.46	11.51		.09	1	25	27	.15					.05
436.9	440.9	33974	4.0	4.0	2E48	4.42	.28	2.52	4.40	9.33		.04	7	27	34	.14					.05
440.9	444.9	33975	4.0	4.0	2E89	4.54	.35	1.07	2.21	6.22		.03	7	32	39	.15					.23
444.9	449.0	33976	4.1	4.1	2E89	4.48	.29	.48	2.34	4.98		.02	9	31	40	.15					.29
449.0	452.2	33977	3.2	3.2	2E19	4.19	.42	.08	1.42	4.04		.05	5	29	35	.15					.15
452.2	455.4	33978	3.2	3.2	2C39	3.92	.80	.17	1.27	10.26		.09	1	26	27	.14					.03
455.4	458.6	33979	3.2	3.2	2C39	3.92	⁴⁰ .29	.67	.59	8.40		.08	1	26	28	.15					.03
458.6	461.0	33980	2.4	2.4	2D43	3.69	.16	3.86	9.57	14.00		.09	3	17	20	.20					.04
461.0	465.7	33981	4.7	4.7	2C3	3.80	.14	.85	2.45	5.91		.08	4	13	17	.17					.09
465.7	470.5	33982	4.8	4.8	2C39	3.89	.44	.28	.92	7.78		.08	3	27	30	.15					.08
470.5	472.2	33983	1.7	1.7	2E41	3.99	.35	1.22	4.91	8.71		.08	5	25	30	.16					.14
472.2	475.9	33984	3.7	3.7	2D39	4.20	⁴⁰ .25	1.86	5.49	9.02		.06	4	27	32	.15					.14
475.9	480.4	33985	4.5	4.5	2C39	3.91	.32	.65	2.65	6.22		.10	4	24	28	.13					.14
480.4	484.8	33986	4.4	4.4	2D39	4.08	.48	1.61	2.68	8.71		.06	6	26	33	.14					.23
484.8	487.0	33987	2.2	2.1	2E41	4.33	.11	4.54	9.63	14.62		.06	4	25	29	.15					.10
487.0	492.0	33988	5.0	5.0	2D43	3.83	²¹ .07	3.42	8.55	20.53		.12	4	17	21	.18					.05

DDH: 84F-21

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														S.G. W.R.
FROM	TO						CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %	
126.0	133.2	33927	7.2	7.0	2C37	3.15	.26	.10	.26	16.17			.03	9	7	16	.20		.05		
133.2	136.6	33928	3.4	3.4	2C37	3.34	.21	.09	.32	11.51			.03	17	7	24	.18		.04		
303.5	305.0	33929	1.5	1.5	2L12	2.90	.03	.22	.32	4.98			.04	2	2	4	.38		.06		
305.0	305.8	33930	.8	.8	2D03	3.17	.10	1.49	4.02	12.44			.08	6	3	9	.26		.04		
305.8	307.8	33931	2.0	2.0	2L14	2.81	.03	.11	.40	1.55			.10	2	2	4	.42		.05		
307.8	309.0	33932	1.2	1.2	2B7	2.82	.04	.27	.97	4.35			.06	2	2	4	.33		.06		
309.0	311.0	33933	2.0	2.0	2L14	2.94	2.11	2.52	2.94	54.43			.30	5	4	9	.29		.05		
311.0	313.6	33934	2.6	2.0	2D37	3.14	.21	3.92	2.89	93.93			.53	5	3	8	.28		.05		

DDH: 84F-22

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													S.G. W.R.
FROM	TO						CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	
47.0	48.3	33935	1.3	1.3	2C39	3.22	.22	.61	.27	46.03		1.71	8	11	19	.18		.02		
55.7	58.1	33936	2.4	2.3	2D0&	3.02	.13	1.80	4.35	33.28		.14	4	5	10	.24		.05		
70.7	75.3	33937	4.6	4.6	2D4&	3.24	.12	4.65	9.60	44.47		.23	5	5	10	.17		.03		
75.3	79.9	33938	4.6	4.6	2D4&	3.52	.09	4.10	11.48	25.51		.17	4	4	8	.17		.02		
79.9	84.6	33939	4.7	4.7	2B0&	2.70	.03	.09	.25	1.87		.02	3	1	4	.30		.13		
89.6	94.6	33940	5.0	5.0	2D0&	3.35	.13	1.71	6.95	17.73		.09	6	8	15	.18		.04		
94.6	99.6	33941	5.0	5.0	2D0&	3.12	.07	1.62	5.42	20.22		.13	3	7	11	.34		.02		
99.6	104.6	33942	5.0	5.0	2D4&	3.46	.09	2.60	8.02	31.73		.14	5	10	16	.26		.03		
104.6	109.5	33943	4.9	4.9	2D9&	3.09	.20	2.23	5.59	32.04			4	6	10	.32		.03		

*include waste
to ore
here* →

21

21

DDH: 84F-23

---DEPTHS---		SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														S.G. W.R.
FROM	TO					Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe %	BAO %	Hg %	Mn %	As %	Ba %	
302.7	304.1	33989	1.4	1.4	2B0	2.84	.08	.18	2.93	3.42			.01	6	3	9	.61			.06
304.1	308.0	33990	3.9	3.9	2C37	3.44	³³ .32	.12	3.05	5.91			.32	11	19	30	.18			.04
308.0	311.8	33991	3.8	3.4	2D43	3.49	.31	.25	9.97	10.58			.39	6	15	22	.17			.04
311.8	314.1	33992	2.3	2.3	2E1&	3.76	.13	.20	1.20	7.78			.14	5	22	27	.15			.06
314.1	315.3	33993	1.2	1.2	2D43	3.40	.09	2.50	8.24	27.37			.25	3	13	16	.20			.08
315.3	318.1	33994	2.8	2.8	2E0	4.70	⁶⁰ .07	.44	.70	6.53			.04	1	35	36	.18			.03
318.1	322.3	33995	4.2	4.2	2E41	4.73	.07	3.26	7.16	41.06			.22	2	28	30	6.51			.09
322.3	325.2	33996	2.9	2.9	2L14	3.36	.15	1.85	3.21	39.19			.20	4	8	12	9.62			.27
325.2	328.8	33997	3.6	3.6	2G41	4.53	.11	6.30	6.40	139.66			.65	7	15	23	13.82			.44
328.8	334.5	33998	5.7	5.7	2L1	3.01	.11	.81	.48	13.06			.09	2	2	5	9.53			.07
334.5	336.2	33999	1.7	1.7	2H49	4.04	.23	6.46	8.17	122.24			.21	16	10	26	3.46			.63
336.2	341.3	34000	5.1	5.1	2L4	3.32	.17	1.46	1.50	36.70			.08	8	8	16	6.30			.19
341.3	344.0	34901	2.7	2.7	2B06	2.86	.04	.74	1.06	15.55			.02	2	2	5	4.51			.07
344.0	346.3	34902	2.3	2.3	0Q0	2.92	.02	.42	1.10	7.15			.02	1		1	2.35			.07
346.3	348.1	34903	1.8	1.8	2B06	3.05	.06	.40	.46	9.33			.08	2	2	5	12.11			.03
348.1	353.6	34904	5.5	5.5	1H41	2.76	^{Wash} .05	.15	.12	4.98			.02	4	2	6	2.15			.07
353.6	357.5	34905	3.9	3.9	2L1	3.03	.07	.28	.66	6.84			.01	3	1	4	6.75			.04
357.5	359.5	34906	2.0	2.0	2L1*	3.28	^{Wash} .07	.12	.30	8.39			.02	3	2	5	25.16			.05
359.5	366.5	34907	7.0	6.8	2L1	2.99	.04	.44	.46	10.26			.02	4	2	7	4.66			.13
366.5	370.8	34908	4.3	4.2	1E19	2.79	.02	.20	.22	4.04			.02	2	1	3	3.55			.05
370.8	372.2	34909	1.4	1.4	2L14	2.97	.04	.85	1.44	18.66			.40	3	2	6	3.52			.11
372.2	373.9	34910	1.7	1.7	1E&9	2.79	.04	.50	.61	10.89			.02	2	1	4	3.83			.07
373.9	378.8	34911	4.9	4.9	2D0&	3.21	.10	3.17	3.24	74.65			.04	9	3	13	3.57			.21
378.8	384.1	34912	5.3	5.3	2E47	4.89	.24	3.19	4.74	64.07			.03	14	15	29	.78			.22
384.1	390.7	34913	6.6	6.6	2L14	3.06	.11	.43	.49	13.37				4	5	9	3.79			.05
390.7	394.4	34914	3.7	3.7	1H4*	3.30	.10	1.25	1.42	31.10			.02	5	5	10	10.72			.07
394.4	398.3	34915	3.9	3.9	2K46	3.61	.28	3.00	7.03	46.66			.04	22	5	27	11.15			.13
398.3	402.6	34916	4.3	4.3	2H49	4.36	⁷⁰ .51	4.54	8.00	48.83			.03	34	18	52	.59			.15
402.6	407.4	34917	4.8	4.8	2H09	4.50	.66	3.27	5.15	42.92			.03	42	28	70	.22			.11
407.4	413.2	34918	5.8	5.8	2E46	4.55	.37	3.76	6.08	47.59			.05	15	27	42	1.33			.10
413.2	418.2	34919	5.0	5.0	2G49	4.76	⁶⁰ .20	.59	7.07	49.77			.03	4	24	28	9.76			.06
418.2	423.2	34920	5.0	5.0	2G4	4.56	.12	3.62	6.30	44.17			.03	2	20	22	20.62			.07
423.2	429.6	34921	6.4	3.4	2G4	4.47	.13	4.91	9.06	53.19			.02	2	14	17	29.83			.08
429.6	434.8	34922	5.2	5.0	2E49	4.76	.45	2.56	4.25	37.64			.20	3	39	43	.68			.10
434.8	441.0	34923	6.2	6.2	2F4L	4.81	⁶⁰ .07	8.09	13.76	60.96			.20	2	29	31	.17			.02
441.0	444.7	34924	3.7	3.7	2E4	4.78	.19	4.89	8.94	41.99			.02	1	35	37	.15			.03
444.7	446.2	34925	1.5	1.5	2E48	4.78	.56	4.03	5.09	39.19			.01	6	36	42	.18			.18
446.2	451.8	34926	5.6	5.6	2E49	4.77	⁶⁰ .50	4.84	4.80	46.66			.03	4	36	40	.17			.12
451.8	457.8	34927	6.0	6.0	2E48	4.83	.33	1.97	2.46	30.17			.03	5	40	46	.31			.16
457.8	462.7	34928	4.9	4.9	2G4	4.63	.14	6.68	8.16	72.47			.04	2	21	24	15.02			.17
462.7	467.1	34929	4.4	4.4	2G4	4.66	.11	5.07	6.60	68.11			.04	3	19	23	18.74			.17
467.1	469.0	34930	1.9	1.9	2E49	4.89	.39	4.42	3.95	49.46			.12	4	34	39	.70			.14
469.0	470.8	34931	1.8	1.8	2E89	4.66	⁵⁰ .49	1.47	2.20	29.86			.20	6	10	17	.34			.18
470.8	475.8	34932	5.0	5.0	2F4	4.71	.07	5.17	10.70	39.50			.02	2	31	33	.16			.02
475.8	481.3	34933	5.5	5.5	2F49	4.71	.20	4.95	11.09	37.64			.02	3	33	36	.15			.09
481.3	487.2	34934	5.9	5.9	2F09	4.90	.28	2.67	5.12	29.24			.02	2	39	41	.15			.05
487.2	488.8	34935	1.6	1.6	2E47	4.41	.46	2.38	3.57	38.26			.04	18	25	43	.23			.13
488.8	491.7	34936	2.9	2.8	2E48	4.69	⁵⁰ .36	2.72	4.50	32.04			.08	5	35	40	.14			.10
491.7	494.0	34937	2.3	2.3	2D39	3.75	.38	4.26	5.89	40.75			.07	9	16	25	.18			.09
494.0	497.0	34938	3.0	3.0	2D09	3.20	.20	2.70	3.45	37.01			.05	7	10	18	.36			.13
497.0	502.0	34939	5.0	5.0	2A4	2.85	.07	2.53	6.27	44.48			1.82	2	4	7	.27			.03

DDH: 84F-23

-----DEPTHS-----				-----ASSAYS-----																	
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %	S.G. W.R.	
502.0	507.2	34940	5.2	2A4	2.80	21.06	2.25	3.41	36.39		.47	2	4	6	.28		.02				
507.2	510.7	34941	3.5	2A0	2.73	.04	.53	1.19	20.53		.05	2	3	5	.54		.02				
510.7	514.4	34942	3.7	2A0	2.69	.05	.69	2.30	23.95		.02	1	3	5	.48		.02				
514.4	518.5	34943	4.1	2B0	2.84	21.07	.21	3.19	22.08		.10	1	3	4	.34		.04				
518.5	520.5	34944	2.0	2A0	2.80	.09	.68	.97	23.02		.10	1	4	5	.35		.01				
520.5	525.0	34945	4.5	2B09	2.94	.50	.24	.85	28.30		.18	3	6	9	.35		.03				

DDH: 84F-24

---DEPTHS---				-----ASSAYS-----																
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
435.5	439.0	34946	3.5	3.5	2A0	2.85	.05	.66	.48	14.00	.12		8	8	.33		.01			
439.0	442.5	34947	3.5	3.3	2A0	2.94	.12	1.13	.36	21.77	.20		10	11	.36		.01			
442.5	443.6	34948	1.1	1.1	2C5	3.22	23.17	.18	.20	13.37	.19	1	12	14	.35		.02			
443.6	446.3	34949	2.7	2.7	2A0	2.84	.08	.92	.88	11.51	.04	2	3	5	.61		.04			
446.3	449.1	34950	2.8	2.5	2A4	2.79	.04	1.69	3.14	18.98	.08	2		3	.43		.05			
449.1	451.8	34951	2.7	2.7	2E41	3.89	50.20	4.76	8.87	74.34	.07	11	14	26	.21		.11			
451.8	455.1	34952	3.3	3.3	2D0	3.02	.08	.76	4.03	15.86	.10	4	3	8	.44		.04			
455.1	458.4	34953	3.3	3.3	2D0	2.94	.05	.54	4.12	11.82	.02	3	2	5	.50		.03			
458.4	459.3	34954	.9	.9	2A0	2.96	.07	.49	2.06	9.95	.03	3	2	5	.38		.02			
459.3	460.3	34955	1.0	1.0	2D5	3.06	.11	1.31	3.56	14.93	.03	3	3	7	.34		.02			
460.3	463.0	34956	2.7	2.7	2A0	2.86	21.07	.50	2.81	13.37	.16	4	2	6	.43		.04			
463.0	466.9	34957	3.9	3.9	2D0	3.06	.16	.73	4.35	25.51	.19	5	5	10	.43		.04			
466.9	468.1	34958	1.2	1.2	2D5	2.92	.07	.57	3.06	14.00	.21	5	2	7	.42		.04			
468.1	470.3	34959	2.2	2.2	2A0	2.82	.06	.20	1.07	10.89	.03	3	2	5	.47		.02			
470.3	471.6	34960	1.3	1.3	2B0&	3.00	.05	.11	.49	6.22	.04	3	2	5	.49		.03			
471.6	472.6	34961	1.0	1.0	2A0	2.91	.05	.34	1.49	10.58	.13	2	1	3	.41		.02			
472.6	473.9	34962	1.3	1.3	2B0	2.89	.06	.09	.55	7.46	.02	3	2	5	.42		.03			
473.9	477.6	34963	3.7	3.7	2A0	2.90	.07	.18	.53	6.22	.02	3	2	6	.43		.02			
477.6	481.3	34964	3.7	3.7	2B0&	2.86	21.04	.71	2.23	11.82	.03	2	1	3	.36		.02			
481.3	485.0	34965	3.7	3.7	2B4&	3.03	.07	1.19	2.91	20.22	.02	3	2	6	.35		.02			
485.0	488.1	34966	3.1	3.1	2D0	3.03	.08	1.44	5.20	34.52	.05	6	2	8	.34		.03			
488.1	491.2	34967	3.1	3.1	2D0	3.01	.10	1.47	3.96	46.03	.15	4	3	8	.37		.03			
491.2	491.8	34968	.6	.6	2C5	3.03	21.07	.79	3.14	23.95	.10	4	6	10	.27		.02			
491.8	495.2	34969	3.4	3.3	2A0	2.78	.08	.26	1.43	14.00	.05	3	2	5	.35		.04			
495.2	498.5	34970	3.3	3.3	2A0	2.84	.07	.61	1.20	11.82	.06	3	5	8	.37		.03			

38 / 493
13.63
4.79

DDH: 84F-25

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														S.G. W.R.
FROM	TO						CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %	
281.5	282.6	35023	1.1	1.1	1E19	2.87	.12	.06	.17	2.80			.04	5	1	6	.30		.05		
282.6	283.9	35024	1.3	1.3	2C09	3.12	.24	.05	.10	5.29			.02	8	6	14	.18		.05		
283.9	287.9	35025	4.0	3.2	2C37	3.45	.41	.04	.12	5.29			.03	14	17	32	.15		.08		
287.9	291.9	35026	4.0	4.0	2C37	3.48	33.48	.01	.36	2.18			.04	22	4	26	.16		.08		
291.9	296.9	35027	5.0	5.0	2C3*	3.57	.19	.04	.43	3.42			.09	5	8	14	.17		.08		
296.9	303.3	35028	6.4	6.4	2C3*	3.34	33.31	.09	.40	4.04			.03	9	14	23	.16		.10		
303.3	304.6	35029	1.3	1.3	2A0	2.87	.11	.06	.09	.93			.02	5	3	8	.52		.10		
349.2	350.8	35030	1.6	1.6	2D09	3.39	.24	2.14	2.62	43.55			.28	6	12	18	.35		.08		
350.8	355.2	35031	4.4	4.4	2G4	4.73	.05	5.04	7.15	105.75			.34	2	18	21	18.91		.10		
355.2	356.4	35032	1.2	1.2	1H4	3.10	.37	1.88	2.98	54.74			.32	5	12	17	5.16		.22		
356.4	358.2	35033	1.8	1.8	2E4	4.54	60.06	2.56	4.58	57.23			.14	4	31	36	.84		.12		
358.2	360.7	35034	2.5	2.5	2L4	2.91	.07	.27	.45	4.67			.02	2	4	7	4.41		.10		
360.7	364.8	35035	4.1	4.1	2E4&	4.36	.05	3.86	5.76	84.91			.12	6	24	31	2.05		.13		
364.8	366.9	35036	2.1	2.1	10E44	3.02	.05	.42	.40	6.53			.02	3	2	6	9.38		.10		
366.9	371.2	35037	4.3	4.3	2E1&	4.52	60.05	2.90	2.92	54.43			.16	3	31	35	2.23		.22		
371.2	375.5	35038	4.3	4.3	2G4	4.36	60.13	5.23	9.50	87.09			.19	7	4	12	26.40		.10		
375.5	381.4	35039	5.9	5.9	2E4&	4.50	20.20	1.31	1.37	37.64			.10	8	31	40	.49		.21		
386.0	387.6	35040	1.6	1.6	2E13	3.57	.28	1.05	1.55	32.97			.33	2	22	25	3.04		.21		
393.8	399.7	35041	5.9	5.9	2E0&	4.66	waste	1.07	.69	21.78			.17	3	36	39	.26		.06		
399.7	405.8	35042	6.1	6.1	2E41	4.67	.06	2.19	1.88	24.58			.10	1	30	32	.22		.03		
405.8	410.0	35043	4.2	3.7	2C3	3.71	.06	.78	.33	32.97		2.19		19	19	.16		.02			
410.0	415.0	35044	5.0	5.0	2C3	3.44	.03	.40	.14	12.44			.60		18	19	.17		.01		
415.0	419.5	35045	4.5	4.5	2E1	4.53	40.06	1.04	1.42	15.24			.15	1	35	36	.14		1.00		
419.5	420.9	35046	1.4	1.4	2E89	4.65	.41	1.88	1.67	24.26			.18	6	34	40	.17		.25		
420.9	423.0	35047	2.1	2.1	2E19	4.69	.23	1.86	2.90	20.84			.06		34	34	.14		.05		
423.0	428.0	35048	5.0	5.0	2F49	4.55	.33	4.82	6.84	50.08			.10	2	29	31	.89		.04		
428.0	433.3	35049	5.3	3.7	2F49	4.90	60.33	5.04	7.30	71.85			.10	4	26	30	3.95		.20		
433.3	435.2	35050	1.9	1.9	2G4	4.52	.12	2.74	7.57	45.72			.05	2	17	19	23.33		.08		
435.2	437.5	35051	2.3	2.3	2E4	4.83	.07	2.18	5.17	23.33			.07	1	34	35	.65		.03		
437.5	441.2	35052	3.7	3.7	2E41	4.18	.24	2.09	2.52	37.64			.08	4	25	29	.28		.20		
441.2	443.8	35053	2.6	2.3	2E4	4.75	50.14	4.63	8.25	56.61			.10	2	30	32	.17		.10		
443.8	448.8	35054	5.0	5.0	2E09	4.66	.27	3.30	2.53	38.57			.06	3	30	34	.15		.13		
448.8	453.8	35055	5.0	5.0	2E49	4.78	.35	2.25	3.04	35.15			.11	3	31	34	.15		.07		
453.8	458.7	35056	4.9	4.9	2E49	4.68	.21	3.32	2.13	8.88			.05	2	31	33	.16		.04		
458.7	464.5	35057	5.8	5.8	2E1	4.31	50.14	1.31	.60	21.15			.05	1	31	33	.15		.21		
464.5	468.5	35058	4.0	4.0	2E41	4.43	.26	2.81	6.06	32.97			.06	5	26	31	.15		.06		
468.5	473.0	35059	4.5	4.3	2E41	4.52	.17	2.18	2.54	23.02			.06	2	31	33	.17		.38		
473.0	478.0	35060	5.0	5.0	2E48	4.49	.33	2.05	3.42	19.59			.05	9	25	34	.15		.28		
478.0	483.0	35061	5.0	5.0	2E48	4.47	.26	2.44	3.83	19.28			.04	7	27	34	.13		.15		
483.0	488.0	35062	5.0	5.0	2E48	4.18	50.42	2.03	2.18	16.17			.06	5	25	31	.15		.18		
488.0	491.4	35063	3.4	3.4	2E48	4.53	.29	2.51	4.02	10.57			.03	6	25	32	.16		.03		
491.4	494.4	35064	3.0	3.0	2E4	4.99	.08	3.53	7.42	18.35			.04	2	32	34	.14		.04		
494.4	498.2	35065	3.8	3.8	2E4	4.88	50.09	2.26	4.60	14.00			.05	2	32	34	.15		.04		
498.2	500.1	35066	1.9	1.9	2E4	4.86	.08	4.04	7.90	22.39			.04	2	32	35	.31		.05		
500.1	501.7	35067	1.6	1.6	2G41	3.57	.32	6.54	12.23	53.50			.07	7	8	16	.28		.04		
501.7	503.5	35068	1.8	1.8	2C09	3.06	.21	1.72	2.07	25.19			.03	6	5	12	.27		.04		
503.5	504.5	35069	1.0	1.0	1D4	2.91	.09	.32	1.31	3.73			.02	3	1	5	.52		.05		
504.5	505.8	35070	1.3	1.3	2C9	3.09	21.20	1.16	1.62	15.86			.05	5		6	.38		.06		
505.8	506.6	35071	.8	.8	1H4	3.36	21.32	.10	1.95	4.98			.04	8	11	20	.62		.07		
506.6	512.0	35072	5.4	5.3	2C59	3.14	.25	.25	.60	5.59			.04	5	6	12	.33		.03		
512.0	518.5	35073	6.5	6.5	2A0	2.80	.06	.35	.93	9.02			.03	2	1	3	.35		.03		

Waste

Waste

DDH: 84F-25

-----DEPTHS-----				-----ASSAYS-----																	
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %	S.G. W.R.	
537.0	542.9	35074	5.9	5.9	0004	3.01	.07	3.04	.46	57.85	.06	1		1	.14		.03				

DDH: 84F-26

---DEPTHS---				---ASSAYS---																
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe %	BAO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
224.7	225.2	34971	.5	.5	2E47	3.48	11	.70	12.27	51.01	.04	15		15	2.14					.08
270.3	271.2	34972	.9	.9	2D39	3.81	1.83	4.27	45.41		.23	8	14	23	.44					.08
271.2	273.4	34973	2.2	.8	2G4	4.66	.05	3.77	7.69	51.01	.06	1	16	18	21.87					.02
273.9	275.1	34974	1.2	1.2	2D4	3.93	.19	4.97	7.47	83.04	.82	2	13	16	.63					.08
292.2	293.5	34975	1.3	.7	2C39	3.65	.21	.51	1.50	11.82	.33	5	16	21	.23					.06
293.5	294.9	34976	1.4	1.4	2D4	4.29	.15	5.85	15.96	44.48	.35	8	6	15	.31					.29
294.9	299.2	34977	4.3	4.3	2D4	3.51	.07	2.75	9.64	21.46	.34	4	7	11	.48					.10
299.6	300.6	34978	1.0	1.0	2D09	3.35	.56	3.57	4.78	127.22	10.55	3	10	14	.27					.10
300.6	301.7	34979	1.1	1.1	2D39	3.56	.40	2.33	2.15	129.70	2.67	7	13	20	.23					.09
301.7	303.2	34980	1.5	1.5	2C39	3.35	.30	1.51	1.36	45.41	.28	10	9	19	.17					.13
303.2	305.7	34981	2.5	2.5	2D48	3.40	.12	5.75	15.40	45.41	.39	2	9	12	.22					.05
305.7	306.2	34982	.5	.5	2D08	3.12	.10	2.08	5.13	19.60	.07	3	9	12	.33					.10
332.8	333.9	34983	1.1	1.1	2C39	3.69	.91	.40	3.07	27.06	.08	12	5	17	.15					.08
333.9	335.4	34984	1.5	1.5	2E17	3.92	.33	.43	1.47	9.64	.02	32	1	33	.15					.08
335.4	340.4	34985	5.0	5.0	2C39	4.14	.24	.47	1.44	9.64	.06	6	19	25	.15					.08
340.4	345.4	34986	5.0	5.0	2C39	3.84	.36	.16	.89	5.29	.08	12	17	29	.15					.08
345.4	350.4	34987	5.0	5.0	2C38	3.71	.12	1.72	2.18	15.87	.11	7	16	24	.20					.04
350.4	355.4	34988	5.0	5.0	2C39	3.53	.34	1.51	2.87	20.22	.21	6	12	18	.24					.05
355.4	358.4	34989	3.0	3.0	2C39	3.24	.64	1.31	.32	33.90	.30	11	7	19	.20					.03
358.4	360.5	34990	2.1	2.1	2C39	3.27	.19	.14	.31	6.84	.04	10	9	20	.21					.08
365.0	368.0	34991	3.0	3.0	2D09	3.26	.46	1.60	3.10	27.06	.93	5	10	16	.26					.08
368.0	370.5	34992	2.5	2.5	2D3	3.51	.11	1.31	3.92	13.37	.26	2	16	18	.22					.03
370.5	375.2	34993	4.7	4.7	2C08	3.26	.06	.37	1.34	7.46	.20	2	14	16	.26					.02
375.2	378.2	34994	3.0	3.0	2C03	3.48	.09	.70	2.62	12.13	.19	2	15	17	.18					.02
378.2	381.6	34995	3.4	3.4	2C39	3.51	.22	2.25	1.09	16.49	.16	2	15	17	.21					.02
381.6	384.7	34996	3.1	3.1	2C38	3.65	.11	.19	.41	7.46	.22	1	18	20	.22					.01
384.7	388.1	34997	3.4	3.4	2C39	3.70	.34	.07	.47	1.56	.10	1	26	28	.16					.01
388.1	391.5	34998	3.4	3.4	2C39	3.89	.22	.06	.88	6.53	.10	1	22	24	.18					.02
391.5	394.9	34999	3.4	3.4	2C3	3.76	.25	.08	.37	6.00	.11	2	22	24	.18					.02
394.9	396.1	35000	1.2	1.2	2A39	3.49	.21	.11	.61	1.87	.12	2	16	19	.22					.03
396.1	399.5	35001	3.4	3.4	2C3	4.03	.07	.05	2.15	4.04	.08	2	24	26	.16					.02
399.5	402.9	35002	3.4	3.4	2C3	3.87	.09	.06	1.22	2.49	.08	1	24	26	.17					.03
402.9	406.3	35003	3.4	3.4	2C38	3.84	.18	.48	2.79	3.11	.08	2	21	23	.18					.08
406.3	409.8	35004	3.5	3.5	2C39	4.00	.34	.44	1.83	4.04	.05	4	22	27	.15					.24
409.8	413.3	35005	3.5	3.5	2E89	4.04	.88	.12	1.32	6.84	.05	9	8	17	.13					.24
413.3	416.8	35006	3.5	3.5	2E89	4.23	.27	.32	1.40	5.29	.10	8	25	34	.14					.16
416.8	418.4	35007	1.6	1.6	2C39	3.65	.37	.05	.57	1.24	.05	7	14	21	.15					.24
418.4	420.7	35008	2.3	2.3	2E89	4.55	.45	.04	1.58	3.73	.06	9	26	35	.14					.14
420.7	423.7	35009	3.0	3.0	2C39	3.78	.48	.47	.94	4.98	.10	6	19	25	.14					.06
423.7	426.4	35010	2.7	2.7	2C39	3.73	.46	.52	.99	5.60	.07	3	17	21	.14					.17
426.4	428.3	35011	1.9	1.9	2C38	4.37	.33	1.37	.87	8.40	.10	6	22	29	.14					.12
428.3	432.0	35012	3.7	3.7	2C3	3.71	.08	.66	1.62	6.53	.11	6	17	24	.14					.03
432.0	433.8	35013	1.8	1.8	2D43	3.83	.06	5.67	7.48	12.75	.10	3	16	20	.16					.02
433.8	437.7	35014	3.9	3.9	2C3	3.66	.06	.24	1.20	1.87	.12	2	19	21	.16					.02
437.7	438.5	35015	.8	.8	2D3	3.64	.06	.37	6.01	2.80	.12	4	16	20	.20					.03
438.5	441.9	35016	3.4	3.4	2D3	3.74	.05	1.53	4.15	8.71	.12	2	18	20	.17					.02
441.9	443.7	35017	1.8	1.7	2E4	4.63	.03	5.15	9.75	36.39	.10	2	29	31	.17					.02
443.7	444.4	35018	.7	.7	2D4	3.52	.06	1.12	10.57	14.93	.14	5	12	17	.22					.04
444.4	445.2	35019	.8	.8	2E0	4.73	.07	.41	1.86	5.91	.06	2	36	38	.13					.02
445.2	445.7	35020	.5	.5	2E4	4.78	.04	1.76	8.19	16.49	.07	6	28	35	.13					.06
445.7	446.4	35021	.7	.7	2D35	3.35	.11	1.75	3.22	26.12	.16	4	14	19	.26					.03

waste

waste

include waste here

waste

23

40

40

21

21

40

40

40

DDH: 84F-27

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													
FROM	TO						CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %
238.7	240.7	35075	2.0	2.0	2C7	3.22	.09	.42	.41	11.20		.05	15		16	.58		.02		
240.7	243.3	35076	2.6	2.6	2C35	3.25	.11	.05	2.22	4.35		.12	22	1	23	.28		.02		
288.1	288.8	35077	.7	.7	2D7	3.01	.07	.74	5.85	6.53		.12	7		8	.24		.04		
316.5	318.0	35078	1.5	1.4	2C57	3.03	.11	.26	.74	6.22		.04	9	3	13	.43		.03		
318.0	318.7	35079	.7	.5	2H41	3.76	.11	1.57	20.21	23.02		.03	22	2	25	.15		.05		
322.6	325.3	35080	2.7	2.7	2C79	3.44	.24	.16	.36	5.91		.14	34	2	36	.17		.02		
325.3	326.5	35081	1.2	1.1	2C57	3.20	.29	.09	.81	3.42		.03	18		19	.21		.03		

Waste
Waste

Include
waste
here

278 - 288.1 Waste
 288.1 - 288.8 As above } 21
 288.8 - 291 waste

DDH: 86F-03

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													S.G. W.R.
FROM	TO						CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe %	BAO %	Hg %	Mn %	As %	
76.5	83.8	34610	7.3	7.3	2C5	3.46	.25	.11	.23	5.00										
83.8	86.5	34611	2.7	2.7	2A0	3.41	.11	.23	.74	3.00										
86.5	94.5	34612	8.0	6.5	2A4	3.38	.09	2.51	8.82	16.00										
94.5	100.5	34613	6.0	5.2	2E741	4.41	.18	6.19	5.72	94.00										
100.5	106.0	34614	5.5	5.0	2D5	3.03	.15	2.08	3.00	30.00										
106.0	111.0	34615	5.0	4.5	2C5	2.66	.08	.98	2.10	15.00										
111.0	116.0	34616	5.0	5.0	2C5	2.94	.08	1.00	1.88	16.00										
116.0	119.5	34617	3.5	3.5	2C5	3.23	.12	.98	2.22	17.00										
119.5	123.5	34618	4.0	4.0	2D5	3.36	.11	2.52	4.55	36.00										
123.5	125.8	34619	2.3	2.3	2H24	4.59	.21	1.93	3.74	32.00										
125.8	131.0	34620	5.2	5.2	2E4	5.44	.08	2.75	4.10	17.00										
131.0	137.8	34621	6.8	6.8	2E4	4.84	.11	3.32	5.38	37.00										
137.8	140.2	34622	2.4	2.4	2H24	4.41	.43	1.87	3.00	24.00										
140.2	144.9	34623	4.7	4.7	2D357	3.46	.20	1.61	4.09	48.00										

14.01
0.13, 4.09, 7.49, 49.42

DDH: 86F-05

-----DEPTHS-----							-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %	S.G. W.R.	
3.5	10.0	34731	6.5	6.5	2C35	3.44	.12	.65	1.46	11.00												
10.0	15.5	34732	5.5	5.5	2D34	3.44	.14	2.47	6.47	13.00												
15.5	19.5	34733	4.0	4.0	1D4	2.80	.06	.11	.08	6.00												
19.5	23.2	34734	3.7	3.7	2C3	3.40	.10	.60	.86	7.00												
24.2	28.0	34735	3.8	3.8	2C3	3.88	.10	1.16	1.22	13.00												
28.0	32.5	34736	4.5	4.5	1D4BX	3.22	.11	1.07	1.10	16.00												
32.5	39.2	34737	6.7	6.7	2D3	3.64	.14	1.89	3.41	17.00												
39.2	46.2	34738	7.0	7.0	2D3	3.68	.19	2.69	3.85	25.00												
46.2	50.0	34739	3.8	3.8	2C3	4.14	.30	.73	.45	10.00												
50.0	54.5	34740	4.5	4.5	2C3	4.26	.41	.70	.46	5.00												
54.5	58.5	34741	4.0	4.0	2D34	3.77	.42	4.23	6.21	37.00												
58.5	70.4	34742	11.9	11.9	1D4	2.88	.03	.10	.10	4.00												
70.4	75.5	34743	5.1	5.1	2C3	3.22	.21	1.24	1.27	20.00												
75.5	81.0	34744	5.5	5.5	2A34	3.78	.04	1.53	4.40	16.00												
81.0	87.0	34745	6.0	6.0	2A4	3.40	.06	4.40	9.94	25.00												
87.0	94.0	34746	7.0	7.0	2A4	3.43	.05	5.46	13.20	38.00												
94.0	101.0	34747	7.0	7.0	2A4	3.51	.07	6.46	7.12	107.00												
101.0	108.0	34748	7.0	7.0	2A4	3.38	.05	3.82	6.57	29.00												
108.0	114.0	34749	6.0	6.0	2A4	3.60	.04	2.56	6.64	23.00												
114.0	120.0	34750	6.0	6.0	2A4	3.24	.06	2.43	6.09	18.00												
120.0	125.0	35151	5.0	5.0	2C0	3.25	.06	.69	1.46	6.00												
125.0	131.0	35152	6.0	6.0	2D0	3.65	.08	1.87	6.61	15.00												
131.0	137.0	35153	6.0	6.0	2C0	3.17	.05	1.10	1.42	12.00												
137.0	143.0	35154	6.0	5.5	2C0	3.16	.07	.73	1.32	9.00												
143.0	149.0	35155	6.0	6.0	2D0	3.26	.08	1.07	3.80	12.00												
149.0	155.3	35156	6.3	5.8	2C0	3.22	.07	.78	1.59	13.00												
155.3	160.0	35157	4.7	4.7	2E4	4.87	.02	2.20	7.01	15.00												
160.0	163.5	35158	3.5	3.5	2E4	4.84		2.78	6.31	16.00												
163.5	167.0	35159	3.5	3.0	2A4	3.48	.03	3.41	8.00	26.00												
167.0	172.5	35160	5.5	5.2	2A4	3.71	.04	5.48	10.00	42.00												
172.5	177.0	35161	4.5	4.1	2A4	3.76	.05	2.34	8.41	28.00												
177.0	179.5	35162	2.5	2.0	2E4	4.58	.03	5.06	9.56	33.00												
179.5	185.0	35163	5.5	5.0	2D34	3.34	.23	4.77	6.67	79.00												
185.0	190.0	35164	5.0	4.2	1D149	2.92	.08	2.38	4.50	35.00												
190.0	193.0	35165	3.0	3.0	2D479	3.23	.16	3.91	9.68	35.00												
193.0	196.0	35166	3.0	3.0	2D479	3.38	.12	1.97	17.60	26.00												
196.0	202.0	35167	6.0	6.0	2D479	3.24	.23	4.24	6.76	43.00												
202.0	207.0	35168	5.0	4.8	2D4	3.40	.08	3.99	11.20	42.00												
207.0	212.0	35169	5.0	5.0	2D4	2.96	.09	2.68	8.20	35.00												
212.0	217.0	35170	5.0	4.6	2D4	3.01	.07	3.41	8.42	44.00												
217.0	222.0	35171	5.0	4.9	2D4	2.94	.06	2.48	7.36	33.00												
222.0	227.0	35172	5.0	5.0	2D4	2.93	.07	2.59	5.69	29.00												
227.0	232.0	35173	5.0	5.0	2D4	3.18	.09	4.90	10.90	55.00												
232.0	237.0	35174	5.0	5.0	2D4	3.56	.05	5.54	11.80	36.00												
237.0	241.0	35175	4.0	3.6	2D4	3.59	.05	5.30	10.20	27.00												
241.0	244.0	35176	3.0	2.8	2D4	3.11	.10	3.68	8.62	34.00												
244.0	249.0	35177	5.0	4.7	1D49	2.83	.06	.81	.44	54.00												

3 2 5
 9 3 12
 11 11
 13 1 14
 3 2 6

DDH: 86F-08

-----DEPTHS-----				-----ASSAYS-----																	
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %	S.G. W.R.	
335.0	338.0	34721	3.0	3.0 2A0 23	2.85	.08	.43	.61	6.00												
338.0	344.5	34722	6.5	6.5 2E4	3.54	.11	4.03	7.56	31.00												
344.5	352.0	34723	7.5	7.5 2E4 50	4.35	.19	5.68	5.80	76.00												
352.0	357.0	34724	5.0	5.0 2E4	4.63	.14	6.30	5.52	82.00												
357.0	361.0	34725	4.0	4.0 2E4	4.59	.12	5.94	4.99	90.00												
361.0	365.5	34726	4.5	4.5 2E4 50	4.41	.18	5.48	5.51	101.00												
365.5	372.0	34727	6.5	6.5 2E47	4.07	.23	4.42	6.53	79.00												
372.0	377.0	34728	5.0	5.0 2D54	3.27	.12	4.58	6.35	102.00												
377.0	378.2	34729	1.2	1.2 2H34	4.26 21	.42	3.77	6.68	83.00												
378.2	382.7	34730	4.5	4.5 2D5	3.02	.19	1.45	3.16	30.00												

40.21
0.17, 5.10, 76.15, 77.59

DDH: 86F-10

-----DEPTHS-----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe %	BAO %	Hg %	Mn %	As %	Ba %	S.G. W.R.	
437.3	439.5	34501	2.2	2.2 2H4	4.42	70.39	5.46	6.99	59.00												
439.5	443.8	34502	4.3	4.3 2A4	3.04	.20	2.17	3.58	38.00												
443.8	447.6	34503	3.8	3.8 2A4	2.87	21.05	1.57	3.42	25.00												
447.6	452.0	34504	4.4	4.4 2A0	2.94	.08	.79	1.18	12.00												
452.0	456.3	34505	4.3	4.3 2A0	3.11	.29	.86	.61	16.00												
456.3	463.6	34506	7.3	7.3 1D4	2.87	Waste		.22	4.00												
463.6	468.2	34507	4.6	4.6 2A0	2.92	.12	1.28	1.39	12.00												
468.2	472.7	34508	4.5	4.5 2A0	2.86	21.06	1.55	2.21	19.00												
472.7	476.7	34509	4.0	4.0 2A4	2.91	.07	3.23	3.56	27.00												
476.7	481.3	34510	4.6	4.6 2A0	3.02	.10	.20	.18	7.00												
402.2	407.0	34844	4.8	4.8 2A0	3.08	.28		.42	5.00												
407.0	413.0	34845	6.0	6.0 2A0	3.10	.41	.37	1.15	8.00												
413.0	419.0	34846	6.0	6.0 2A0	3.32	23.28	.11	.80	6.00												
419.0	424.0	34847	5.0	5.0 2A0	2.99	.07	1.07	2.81	16.00												
424.0	428.5	34848	4.5	4.5 2E4	4.24	.16	4.29	7.24	50.00												
428.5	433.2	34849	4.7	4.7 2E4	4.67	50.21	5.85	8.34	61.00												
433.2	437.3	34850	4.1	4.1 2E4	4.69	.10	5.36	8.47	50.00												

10.3'
0.19
2.65
4.25
32.69

START

13.3' .16 5.17 8.01 53.89

23.6'
0.17, 4.07, 6.37, 46.82
10.49

DDH: 86F-11

-----DEPTHS-----							-----ASSAYS-----													
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
165.2	169.0	35201	3.8	3.8	2G74	4.20		5.47	7.87	95.00	.10	12	14	27						
169.0	173.5	35202	4.5	4.5	1H4	2.90	80	1.31	.87	24.00	.07	6	5	12						
173.5	180.9	35203	7.4	3.7	1H4	3.70		4.19	3.47	69.00	.07	16	13	29						
180.9	184.8	35204	3.9	3.9	2E4*	4.20	80	8.66	8.15	140.00	.24	12	19	31						
184.8	193.0	35205	8.2	6.7	1H4	3.20		2.72	2.75	14.00	1.17	5	8	13						
193.0	198.0	35206	5.0	3.9	2E46	4.50	60	2.07	2.47	17.00	.55	2	35	37						
198.0	202.0	35207	4.0	4.0	2E0	4.80		1.59	1.54	16.00	.03	3	37	41						
202.0	207.0	35208	5.0	4.3	2E0	4.30		.35	.15	14.00	.03	1	36	37						
207.0	211.0	35209	4.0	3.0	2E0	4.50	40	.72	.19	9.00		1	39	41						
211.0	217.0	35210	6.0	3.9	2E0	4.50		.31	.16	5.00		1	40	41						
217.0	223.0	35211	6.0	3.7	2E4	5.00		2.74	3.15	12.00	.21	1	39	41						
223.0	228.5	35212	5.5	5.5	2E18	4.80		.90	.73	24.00	.69	5	36	41						
228.5	233.5	35213	5.0	5.0	2E80	4.50	40	1.45	.40	20.00	.14	6	35	41						
233.5	238.3	35214	4.8	4.8	2E48	4.80		2.75	2.47	36.00	.17	5	36	42						
238.3	243.5	35215	5.2	5.2	2E80	4.50		.45	.33	9.00	.03	7	34	42						
243.5	246.6	35216	3.1	3.1	2GE4	4.50	40	4.39	4.48	73.00		7	24	31						
246.6	251.0	35217	4.4	4.4	2E0	4.30		1.14	1.14	11.00		12	28	40						
251.0	255.9	35218	4.9	4.2	2E0	4.30		.66	.56	11.00		10	31	42						
255.9	260.4	35219	4.5	4.5	2E0	4.55	40	.82	.56	15.00		8	33	42						
260.4	265.0	35220	4.6	4.6	2E0	4.50		1.79	1.78	20.00		6	33	40						
265.0	271.0	35221	6.0	6.0	2E0	4.80		1.33	2.19	16.00		4	36	41						
271.0	277.5	35222	6.5	5.9	2E4	4.50		2.84	3.15	26.00		2	39	42						
277.5	283.0	35223	5.5	5.5	2E814	4.50	21	2.15	3.27	22.00		5	32	38						
283.0	286.5	35224	3.5	3.5	2E814	4.30		3.15	4.86	18.00		5	28	33						
286.5	291.0	35225	4.5	4.5	2E814	4.30		2.27	3.05	60.00		5	32	37						
291.0	296.0	35226	5.0	5.0	2E814	4.50		2.37	4.71	7.00		5	31	37						
296.0	303.0	35227	7.0	7.0	2A43	3.80	21	2.75	7.83	36.00		4	17	21						
303.0	307.8	35228	4.8	4.8	2ED	4.00		1.01	.92	27.00		9	25	34						
307.8	312.2	35229	4.4	4.4	2D5	4.00		3.74	7.60	18.00		19	10	30						

DDH: 86F-12

---DEPTHS---				S.G.		-----ASSAYS-----																		
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %	S.G. W.R.				
185.6	190.3	35230	4.7	4.7	2E341	3.70		2.17	5.20	24.00		10	17	28										
190.3	194.5	35231	4.2	3.6	2C07	3.00	33	.40	.20	8.00		.07	4	4	9									
194.5	199.0	35232	4.5	4.5	2C07	3.00		.26	.42	6.00		.45	4	11	15									
199.0	204.0	35233	5.0	5.0	2C37	3.70	33	.24	.75	4.00		.38	2	25	28									
204.0	209.0	35234	5.0	5.0	2C37	3.70		.75	2.02	10.00		.34	2	23	26									
209.0	213.9	35235	4.9	4.7	2G4	4.50		6.40	6.98	70.00		.58	4	22	26									
213.9	217.5	35236	3.6	3.6	2G4	4.80	60	7.36	6.56	74.00		.24	6	22	29									
217.5	222.1	35237	4.6	4.6	2G4	4.80		6.42	6.87	74.00		.14	2	20	22									
222.1	227.1	35238	5.0	4.8	2G4	4.50		7.60	6.87	90.00		.27	4	24	29									
227.1	231.7	35239	4.6	4.6	2G4	4.80	60	5.66	6.65	80.00		.24	1	23	24									
231.7	235.8	35240	4.1	4.1	2G4	4.80		5.86	6.89	98.00		.21	3	19	22									
235.8	238.7	35241	2.9	2.9	2H43	4.30		4.45	6.73	70.00		.14	17	15	33									
238.7	243.2	35242	4.5	4.5	1D219	3.00		.73	.84	12.00		.14	2	4	7									
243.2	247.0	35243	3.8	3.8	1D219	3.00	Wash	.52	.66	4.00		.03	2	2	4									
247.0	252.0	35244	5.0	4.6	1D219	3.00	110	.75	1.09	14.00		.07	3	3	7									
252.0	256.0	35245	4.0	4.0	1D19*	3.00		1.94	1.83	44.00			3	5	8									
256.0	260.7	35246	4.7	4.7	BXA	3.70		.42	3.46	94.00			14	14	28									
260.7	264.5	35247	3.8	3.8	2H43	4.50		6.46	8.88	104.00			18	17	35									
264.5	268.5	35248	4.0	4.0	2H43	4.30		6.63	8.51	98.00			26	12	39									
268.5	271.5	35249	3.0	3.0	2A4	3.30	70	2.37	7.24	38.00			6	6	13									
271.5	275.5	35250	4.0	4.0	2H43	4.30		5.66	7.84	74.00			16	20	37									
275.5	279.8	35251	4.3	4.3	1D419	2.90		.77	.69	18.00		.24	3	3	7									
279.8	282.8	35252	3.0	3.0	2EH	4.20		5.19	3.42	70.00		.03	13	21	35									
282.8	288.8	35253	6.0	6.0	2E4	4.80	60	4.26	4.47	32.00		.07	2	36	39									
288.8	292.0	35254	3.2	3.1	2G4	4.50		6.11	7.22	42.00			2	18	21									
292.0	295.7	35255	3.7	3.7	2G4	4.50		6.29	7.56	50.00			2	20	23									
295.7	301.0	35256	5.3	2.3	2F4	4.80		1.57	3.16	8.00			3	40	44									
301.0	305.0	35257	4.0	4.0	2F4	4.50	50	5.92	10.10	40.00			1	34	35									
305.0	309.8	35258	4.8	4.8	2F4	4.80		3.95	6.52	20.00		.03	5	34	40									
309.8	314.0	35259	4.2	4.2	2E81	4.50	40	.97	1.95	10.00			5	37	43									
314.0	323.2	35260	9.2	.7	2E81	5.00		1.54	1.43	10.00			5	38	43									
323.2	327.0	35261	3.8	3.5	2E4	4.80		4.11	7.00	20.00			3	37	41									
327.0	332.0	35262	5.0	5.0	2E4	4.80	50	2.95	4.21	20.00			3	38	42									
332.0	335.9	35263	3.9	3.9	2E4	5.00		2.25	2.67	12.00			3	39	43									
335.9	342.0	35264	6.1	2.1	2E0	4.80		1.95	2.23	10.00			3	41	45									
342.0	347.8	35265	5.8	4.6	2E4	4.80	50	2.32	5.33	14.00			3	39	42									
347.8	352.8	35266	5.0	5.0	2E4	5.00		2.75	5.65	16.00		2.85	2	41	43									
352.8	357.7	35267	4.9	4.9	2E0	4.30		1.37	1.44	12.00			1	33	34									
357.7	362.4	35268	4.7	4.7	2E4	5.00	50	3.23	5.14	22.00			1	40	42									
362.4	366.8	35269	4.4	4.4	2E4	4.80		2.66	5.15	18.00			4	35	40									
366.8	370.2	35270	3.4	3.4	2AE4	3.40		1.73	4.01	18.00			5	11	17									
370.2	374.2	35271	4.0	4.0	2AE4	3.70		3.00	5.05	30.00		.07	5	16	21									
374.2	378.4	35272	4.2	4.2	2D5	3.10	21	2.04	3.28	26.00			5	7	13									
378.4	383.6	35273	5.2	5.0	2D5	3.00		3.33	4.22	44.00			5	5	11									
383.6	387.9	35274	4.3	4.3	2A43	4.50		6.67	7.25	60.00		.24	2	36	38									
387.9	393.0	35275	5.1	5.1	2A4	3.40		1.84	3.69	22.00		.03	2	1	3									
393.0	398.5	35276	5.5	5.2	2A4	2.80	21	2.11	2.75	22.00		.03	2	1	3									
398.5	403.5	35277	5.0	5.0	2A4	2.80		1.76	4.46	30.00		.48	1		2									
403.5	407.0	35278	3.5	.5	2A4	2.70		2.28	3.72	36.00		.14	2	2	4									
407.0	411.8	35279	4.8	4.8	2A4	3.10		1.06	1.34	16.00		.38	2	2	5									
411.8	416.2	35280	4.4	4.4	2A43	4.70	21	8.67	8.65	129.00		.72	4	28	33									

DDH: 86F-12

							-----ASSAYS-----														
----DEPTHS----		SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %	S.G. W.R.	
FROM	TO																				
416.2	420.7	35281	4.5	4.5	2A4	2.90		1.20	2.62	22.00			.51	1	5	6					
420.7	425.3	35282	4.6	4.6	2A4	3.30		1.61	3.28	34.00			.72	1	7	8					
425.3	430.0	35283	4.7	4.7	2A4	3.20		4.50	4.06	106.00			.96	1	9	11					
430.0	434.5	35284	4.5	4.5	2A4	3.30	21	1.17	3.33	30.00			.69		13	14					
434.5	439.0	35285	4.5	4.5	2A4	3.00		1.52	3.29	34.00			.51	1	8	9					
439.0	443.0	35286	4.0	4.0	2A4	3.00		1.31	3.34	30.00			.14	2	7	9					
443.0	448.0	35287	5.0	5.0	2A43	4.40	21	1.44	4.86	22.00			.27	5	15	20					
448.0	452.8	35288	4.8	4.8	2A4	3.10		1.63	4.06	26.00			.07	3	5	9					
452.8	457.4	35289	4.6	4.6	2A4	2.90		1.31	4.84	20.00			1.47	3	2	5					

DDH: 86F-14

---DEPTHS---		SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													
FROM	TO					CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %
102.7	108.0	35333	5.3	4.7	2GL	4.20	3.82	4.50	44.00		.10	8	19	27					
108.0	111.5	35334	3.5	3.4	2J814 ⁵⁰	4.00	2.71	2.01	14.00			41		41					
111.5	118.0	35335	6.5	6.5	2E4	4.40	3.30	3.00	44.00			5	33	39					
118.0	126.0	35336	8.0	6.5	2E4	4.30	3.87	4.04	52.00			17	19	37					
126.0	132.2	35337	6.2	6.2	2E0 ⁵⁰	4.60	1.82	1.36	26.00		.27	12	28	41					
135.2	139.8	35338	4.6	3.3	2E4	4.50	8.26	8.46	88.00		.27	2	28	30					
139.8	144.0	35339	4.2	3.8	2E0 ⁴⁰	4.50	.56	.35				12	26	39					
144.0	150.2	35340	6.2	6.2	2E4	4.40	2.94	3.09	28.00			4	33	38					
150.2	156.5	35341	6.3	6.3	2E44 ⁵⁰	4.30	5.91	8.23	50.00			1	33	35					
156.5	161.0	35342	4.5	4.4	2E0 ⁴⁰	4.70	1.25	1.74	16.00			6	33	40					
161.0	165.2	35343	4.2	4.2	2E0	4.70	.95	1.68	12.00			4	34	39					
165.2	170.2	35344	5.0	5.0	2E0	4.70	1.24	2.25	10.00			4	34	39					
170.2	174.7	35345	4.5	3.7	2E4 ⁵⁰	4.50	1.42	2.94	8.00			4	31	35					
174.7	180.0	35346	5.3	5.0	2E4BX	4.50	2.71	4.05	10.00			6	27	33					
180.0	185.0	35347	5.0	5.0	2E4	4.60	2.67	4.74	26.00				38	39					
185.0	190.4	35348	5.4	5.4	2E4	4.60	3.75	6.34	14.00			1	38	39					
190.4	195.0	35349	4.6	4.6	2E4 ⁵⁰	4.50	2.66	3.59	12.00				40	41					
195.0	199.5	35350	4.5	4.5	2E4	4.70	4.22	9.28	18.00			1	33	35					
199.5	204.0	35351	3.0	3.0	2J81	4.00	1.15	1.26	8.00			43	3	46					
204.0	209.5	35352	4.5	4.5	2E4 ⁵⁰	4.70	2.28	5.99	8.00		.21	1	38	40					
209.5	215.0	35353	5.5	5.5	2E14	4.50	2.71	5.70	10.00			3	32	36					
215.0	220.0	35354	5.5	5.5	2E4	4.80	3.33	6.72	8.00			1	37	38					
220.0	225.0	35355	5.0	5.0	2A47 ⁷⁰³	3.60	3.03	5.80	38.00			17	8	26					
225.0	229.0	35356	5.0	5.0	2D57	3.10	1.47	2.80	14.00		.03	8	4	13					
229.0	233.0	35357	4.0	3.9	2C79 ²¹	3.30	.11	1.18			.03	5	11	17					
233.0	237.5	35358	4.0	4.0	2C579	3.30	.44	1.35	4.00			29	4	34					
237.5	243.5	35359	4.5	4.5	2D79	3.50	1.56	5.11	16.00		.07	9	13	22					
243.5	248.0	35360	6.0	6.0	2A44 ²¹	3.90	4.95	9.79	36.00		.14	2	18	21					
248.0	253.5	35361	4.5	4.5	2A44	3.20	4.05	9.18	18.00		.14	4	8	12					

DDH: 86F-15

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	---ASSAYS---		Ba %	S.G. W.R.
FROM	TO														TOT Fe	BAO %		
128.0	133.5	35362	5.5	5.5	2E4	4.40		2.01	2.85	38.00		.07	9	26	35			
133.5	135.5	35363	2.0	2.0	2G4	4.30		3.50	7.25	63.00			1	17	18			
135.5	141.3	35364	5.8	3.9	2E4	4.60	60	6.40	8.28	110.00		.07	11	20	31			
141.3	145.1	35365	3.8	3.8	2E4	4.20		5.72	8.32	95.00		.07	14	20	34			
145.1	148.3	35366	3.2	3.2	2D43	3.70		3.79	8.49	69.00		.07	13	11	24			
148.3	153.0	35367	4.7	4.7	2C0	3.00		.17	.18	8.00			4	5	10			
153.0	157.5	35368	4.5	4.4	1H49	3.10		.21	.22	6.00			5	3	8			
157.5	162.5	35369	5.0	4.9	2C03	3.50		1.71	.50	53.00			14	18	33			
162.5	166.5	35370	4.0	4.0	1H4*9	4.00		4.33	4.27	80.00		.03	10	14	24			
166.5	172.5	35371	6.0	6.0	1H49	2.80		.39	.22	8.00			9	5	14			
172.5	177.0	35372	4.5	4.3	1E19	2.80	Waste	.25	.29	6.00		.03	1	2	4			
177.0	182.4	35373	5.4	5.4	1E19	3.00		.59	.92	10.00		.27	2	4	6			
182.4	187.0	35374	4.6	4.6	1D49	3.20	130	1.02	.46	21.00		.27	3	5	8			
187.0	191.8	35375	4.8	4.7	1D49	3.10		1.22	1.58	25.00		.21	3	4	7			
191.8	195.3	35376	3.5	3.4	1H49	3.70		3.64	4.30	57.00			11	13	25			
195.3	198.8	35377	3.5	3.5	1H49	3.00		1.79	.47	34.00			3	2	6			
198.8	203.8	35378	5.0	5.0	1E19	2.90		.26	.48	6.00			1	2	4			
203.8	209.8	35379	6.0	5.5	1D9	3.10	Waste	.67	1.44	11.00			5	6	11			
209.8	214.3	35380	4.5	4.5	1D9	2.90	100	.65	1.11	11.00			2	2	5			
214.3	219.4	35381	5.1	5.1	1D9	3.10		.97	1.09	15.00			2	5	8			
219.4	224.7	35382	5.3	4.2	2E4	4.50	60	4.24	4.33	51.00			2	29	31			
224.7	228.2	35383	3.5	3.5	2E4	3.40		7.18	4.71	118.00			7	9	16			
228.2	233.5	35384	5.3	2.0	2E1	4.50		2.13	1.58	27.00				38	39			
233.5	238.5	35385	5.0	1.8	2E1	4.00	40	.48	.28	10.00				31	32			
238.5	246.0	35386	7.5	6.2	2E1	3.70		.60	.39	30.00				25	26			
246.0	251.5	35387	5.5	5.0	2E1	4.10		1.09	.51	76.00				34	35			
251.5	258.5	35388	7.0	3.1	2E1	4.20	40	.47	.15	11.00			1	34	35			
258.5	264.5	35389	6.0	4.6	2E1	4.40		1.24	.97	17.00			2	35	38			
264.5	269.5	35390	5.0	3.5	2E1	4.40		1.39	1.18	17.00				37	38			
269.5	276.2	35391	6.7	4.7	2E1	4.00	40	.61	.95	11.00			1	34	36			
276.2	280.5	35392	4.3	4.3	2E14	4.70	40	2.67	1.69	30.00			2	41	43			
280.5	284.5	35393	4.0	4.0	2E1	4.70		1.24	1.98	17.00			3	39	43			
284.5	289.0	35394	4.5	4.5	2F4	5.00		6.50	7.25	30.00			4	33	38			
289.0	294.3	35395	5.3	5.3	2F4	4.50	50	5.44	8.12	21.00			5	30	36			
294.3	298.0	35396	3.7	3.7	2F4	4.90		3.43	6.47	17.00			3	36	40			
298.0	302.2	35397	4.2	4.2	2F4	4.60		3.49	7.74	19.00			2	36	39			
302.2	307.1	35398	4.9	4.9	2F4	4.60		4.40	8.50	22.00			5	29	35			
307.1	310.9	35399	3.8	3.8	2F4	4.60	50	7.75	12.97	46.00			7	23	30			
310.9	314.5	35400	3.6	3.6	2F4	4.70		7.58	11.23	60.00			7	24	32			
314.5	318.5	35401	4.0	4.0	2F4	4.70		5.79	6.80	48.00			6	28	34			
318.5	322.8	35402	4.3	4.3	2E4	4.70		2.17	3.55	17.00			5	34	39			
322.8	327.0	35403	4.2	4.2	2E4	4.70		5.82	8.71	26.00			2	33	36			
327.0	331.2	35404	4.2	4.2	2E4	5.00	50	2.14	5.21	13.00			1	39	40			
331.2	335.1	35405	3.9	3.9	2E0	4.90		1.03	1.91	11.00				43	44			
335.1	339.6	35406	4.5	4.5	2E0	4.90		.19	1.97	6.00				46	47			
339.6	345.5	35407	5.9	5.0	2E4	4.90		3.55	6.42	20.00				41	42			
345.5	348.8	35408	3.3	3.3	2E4	4.90	50	5.31	10.02	32.00			1	37	39			
348.8	353.5	35409	4.7	4.7	2E4	4.90		3.49	9.26	23.00			2	36	38			
353.5	357.5	35410	4.0	4.0	2E4	4.50		1.90	3.90	22.00			6	32	38			
357.5	360.1	35411	2.6	2.6	2H34	4.60		6.16	9.25	40.00			12	26	38			
360.1	365.5	35412	5.4	5.4	2D3	3.60		2.37	5.34	20.00			7	12	19			

DDH: 86F-15

-----DEPTHS-----							-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP		CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %	S.G. W.R.	
365.5	370.5	35413	5.0	5.0	2C05	3.00	21	1.23	2.24	18.00				4	3	7						
370.5	375.0	35414	4.5	4.4	2A4	3.00		1.56	4.29	21.00				2	2	5						
375.0	384.0	35415	9.0	8.9	1D419	2.90		.04	.06	2.00				4	1	5						
384.0	387.8	35416	3.8	3.8	2A0	3.10	21	.24	.66	10.00				3	9	13						
387.8	392.7	35417	4.9	4.7	2A0	3.10		.19	.75	11.00				6	7	13						
392.7	396.8	35418	4.1	4.1	2A0	3.10		.11	.42	7.00				5	6	12						
396.8	401.4	35419	4.6	4.6	1D09	2.80	21	.34	.25	21.00				2	3	5						
401.4	406.5	35420	5.1	5.1	2A0	3.00		.20	.39	6.00				2	3	6						
406.5	410.7	35421	4.2	4.2	2A0	3.00		.26	1.58	8.00				3	4	8						

DDH: 86F-16

							-----ASSAYS-----															
---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	CU	Pb	Zn	Ag(AA)	Ag(FA)	Au(FA)	Po	Py	TOT	BAO	Hg	Mn	As	Ba	S.G.	
FROM	TO						%	%	%	g/mT	g/mT	g/mT	%	%	%	%	%	%	%	%	%	%
11.0	18.5	34551	7.5	7.5	2G4	4.50		6.58	7.70	91.00		.21	3	13	17							
18.5	25.5	34552	7.0	6.7	2E14	4.60	60	1.69	2.45	19.00		.10		35	36							
25.5	29.5	34553	4.0	4.0	2G4	4.70		4.37	8.05	44.00		.03		26	26							
29.5	33.5	34554	4.0	4.0	2G4	4.70		4.34	7.42	44.00		.07		26	27							
33.5	37.0	34555	3.5	3.5	2E4	4.60	60	2.10	3.86	26.00		.17	2	37	39							
37.0	40.5	34556	3.5	3.4	2E4	4.90		3.35	4.20	27.00		.07		36	36							
40.5	45.5	34557	5.0	5.0	2C3	3.60		.11	.17	2.00		.03		28	28							
45.5	50.6	34558	5.1	5.1	2C3@	4.10	40	.52	.60	6.00		.10		33	34							
50.6	57.0	34559	6.4	6.4	2E1	4.30		.76	1.10	10.00		.10	1	32	33							
57.0	62.6	34560	5.6	4.2	2E1	4.90	40	1.40	1.54	12.00		.07		45	46							
62.6	67.8	34561	5.2	5.2	2E1	4.50		.82	.41	18.00		.17		38	39							
67.8	69.5	34562	1.7	1.7	2E14	4.00		3.94	4.49	49.00		.34	1	22	24							
69.5	75.0	34563	5.5	5.5	2E484	4.50		5.57	7.72	25.00		.10	5	28	34							
75.0	80.0	34564	5.0	5.0	2E484	4.80	50	9.22	13.60	45.00		.10	6	24	31							
80.0	84.6	34565	4.6	4.6	2E484	5.00		6.12	9.07	40.00		.21	7	33	40							
84.6	88.3	34566	3.7	3.7	2E8	4.80		.66	1.82	8.00		.17	6	35	42							
88.3	93.0	34567	4.7	4.7	2E1	3.90	50	.63	1.23	16.00		.65	1	29	31							
93.0	98.2	34568	5.2	5.2	2D443	4.60		9.81	13.63	28.00		.21	3	20	24							
98.2	101.7	34569	3.5	3.5	2C3	4.30		.16	.68	4.00		.27	1	32	33							
101.7	105.0	34570	3.3	3.3	2D3	3.90	50	2.93	1.99	36.00		1.51		27	28							
105.0	109.0	34571	4.0	4.0	2D3	3.70		1.41	5.33	12.00		.24	1	25	27							
109.0	113.5	34572	4.5	4.5	2D3	3.80		.53	3.76	8.00		.17	2	24	26							
113.5	116.5	34573	3.0	3.0	2C3	3.70	40	.38	.82	12.00		.31		28	28							
116.5	120.0	34574	3.5	3.5	2E81	4.10		.87	2.49	6.00		.10	5	28	34							
120.0	124.5	34575	4.5	4.5	2E481	4.00		8.89	16.00	17.00		.10	6	19	25							
124.5	129.5	34576	5.0	5.0	2E481	3.90	50	4.69	4.97	7.00		.14	4	20	25							
129.5	134.8	34577	5.3	5.3	2E481	4.00		6.01	6.53	10.00		.14	5	17	22							
134.8	139.0	34578	4.2	4.2	2E81	3.90		.16	2.28	2.00		.10	5	23	29							
139.0	144.0	34579	5.0	5.0	2E81	3.90		.14	1.10	4.00		.10	5	24	29							
144.0	149.4	34580	5.4	5.4	2E81	4.30	40	.10	1.80	6.00		.07	8	32	40							
149.4	152.0	34581	2.6	2.5	2C3	3.60		.29	1.91	12.00		.03	4	19	23							
152.0	154.8	34582	2.8	2.8	2E81	4.40		.24	1.56	4.00			5	36	41							
154.8	159.0	34583	4.2	4.2	2E481	4.20		2.60	6.09	6.00			5	27	33							
159.0	164.0	34584	5.0	5.0	2E481	4.40	50	1.22	3.40	6.00			6	29	36							
164.0	168.0	34585	4.0	4.0	2E814	4.40		1.91	2.46	8.00		.07	3	32	35							
168.0	172.6	34586	4.6	4.6	2E81	4.40		.12	1.12	4.00		.07	5	36	42							
172.6	177.0	34587	4.4	4.4	2E41	4.50		3.92	8.68	10.00		.03	2	30	32							
177.0	182.0	34588	5.0	4.5	2E41	4.70	50	6.71	11.96	19.00		.03	1	34	36							
182.0	187.0	34589	5.0	4.7	2EA4	4.10		1.54	5.94	8.00		.07	1	31	32							
187.0	191.0	34590	4.0	4.0	2EA4	4.10		1.84	6.84	10.00		.10		29	30							
191.0	198.0	34591	7.0	4.7	2A34	3.80		4.56	7.76	21.00			1	37	38							
198.0	202.6	34592	4.6	4.6	2A34	4.10	21	1.63	7.19	11.00		.07		25	26							
202.6	208.6	34593	6.0	6.0	2A34	3.80		2.75	6.05	16.00		.07		20	21							
208.6	215.0	34594	6.4	6.4	2E4	4.70		5.36	9.42	6.00		.03	1	36	37							
215.0	222.5	34595	7.5	7.5	2D345	3.80	21	3.56	7.56	10.00		.17	3	19	22							
222.5	228.2	34596	5.7	5.7	2C0	3.20		.61	1.12	24.00		.14	6	9	16							
228.2	234.0	34597	5.8	5.8	2D0	.50		.15	5.94	6.00		.03	3	13	17							
234.0	238.7	34598	4.7	4.7	2A34	4.00		5.15	12.32	38.00		.17	2	19	22							
238.7	244.8	34599	6.1	6.1	2E14	4.00	21	3.27	4.34	28.00		.14	5	26	31							
244.8	249.0	34600	4.2	4.2	2C0	3.30		.77	.61	15.00		.14	4	7	12							
249.0	253.8	35083	4.8	4.7	2C0	3.20	21	.26	.51	9.00		.14	3	12	16							

DDH: 86F-16

---DEPTHS---				-----ASSAYS-----																	
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %	S.G. W.R.	
253.8	259.2	35084	5.4	5.4	2C5	2.90	.49	1.72	13.00		.34	5	6	11							
259.2	265.5	35085	6.3	6.3	1D194	2.80	.54	.18	17.00		.17	3	2	5							
265.5	271.5	35086	6.0	6.0	1D194	2.80	.22	.40	7.00		.03	1	2	3							

DDH: 86F-17

							-----ASSAYS-----															
DEPTH	DEPTH	SAMPLE	INT.	REC.	ROCK	S.G.	CU	Pb	Zn	Ag(AA)	Ag(FA)	Au(FA)	Po	Py	TOT	BAO	Hg	Mn	As	Ba	S.G.	
FROM	TO	NO.			UNIT	PULP	%	%	%	g/mT	g/mT	g/mT	%	%	Fe	%	%	%	%	%	W.R.	
290.0	295.1	04964	5.1	5.1	2B45	3.20		2.95	6.76	42.00				3	1	5						
295.1	300.0	04965	4.9	4.9	2B45	3.00	21	2.09	7.27	38.00				2	1	3						
300.0	305.0	04966	5.0	5.0	2C0	3.00		.86	2.52	19.00				3	4	7						
223.0	226.0	35087	3.0	3.0	2D05	3.10		3.24	2.37	44.00				6	10	16						
226.0	230.6	35088	4.6	4.6	2B4	2.90		2.04	6.72	30.00				2	1	4						
230.6	235.5	35089	4.9	4.9	2B4	2.80	21	1.86	3.47	24.00				2	2	5						
235.5	240.3	35090	4.8	4.8	2B4	3.00		4.46	4.12	50.00				3	3	6						
240.3	244.7	35091	4.4	4.4	2B4	2.90		3.64	5.15	36.00				2	2	5						
244.7	249.0	35092	4.3	4.3	2B4	3.00	21	3.43	8.66	46.00				3	1	4						
249.0	252.5	35093	3.5	3.5	2A4	3.00		4.20	9.31	58.00				2	2	4						
252.5	255.5	35094	3.0	3.0	2B45	3.00		1.10	3.35	32.00				2	3	6						
255.5	266.0	35095	10.5	9.3	1D419	3.00	Waste	1.99	4.48	94.00				3	2	5						
266.0	270.7	35096	4.7	4.7	2B45	3.00		3.81	6.12	76.00				2	2	5						
270.7	275.3	35097	4.6	4.6	2B45	3.00	21	3.29	5.15	32.00				3	3	7						
275.3	280.2	35098	4.9	4.9	2B45	3.00		4.67	6.78	60.00				2	1	4						
280.2	285.1	35099	4.9	4.9	2B45	3.10		4.28	10.51	52.00				2	1	3						
285.1	290.0	35100	4.9	4.9	2B45	3.00		4.87	4.99	50.00				3	2	6						
168.7	173.0	35141	4.3	4.3	2D354	3.80		3.39	9.43	20.00				1	23	24						
173.0	178.0	35142	5.0	5.0	2D35	3.50	21	2.95	6.77	28.00				3	17	20						
178.0	183.0	35143	5.0	5.0	2AD	3.20		1.54	2.76	22.00				3	10	14						
183.0	188.0	35144	5.0	5.0	2C05	3.10		1.12	2.60	16.00				2	4	6						
188.0	193.0	35145	5.0	5.0	2C05	2.90		.36	.98	10.00				3	8	11						
193.0	198.0	35146	5.0	5.0	2C05	3.00	21	.63	1.81	12.00				2	9	11						
198.0	203.0	35147	5.0	5.0	2C05	3.20		.29	.95	6.00				6	14	20						
203.0	211.5	35148	8.5	7.5	2C05	3.30		.69	2.68	14.00				4	15	19						
211.5	218.5	35149	7.0	5.3	2C05	3.30	21	.36	.35	18.00				4	16	20						
218.5	223.0	35150	4.5	3.4	2D05	3.50		3.23	5.10	40.00				4	15	20						
7.0	11.5	35470	4.5	4.5	2GAC	3.60		4.20	12.52	42.00				3	15	19						
11.5	17.0	35471	5.5	4.7	2A4	3.50	33	2.14	5.84	26.00				2	16	19						
17.0	21.8	35472	4.8	4.8	2A4	3.60		3.15	6.07	68.00					18	19						
21.8	26.0	35473	4.2	4.2	2C3	4.10		.35	1.25	12.00				1	36	37						
26.0	31.0	35474	5.0	5.0	2C3	4.10	40	.13	.72	6.00				2	36	39						
31.0	36.0	35475	5.0	5.0	2C3	4.00		.39	1.37	8.00				4	30	34						
36.0	42.0	35476	6.0	6.0	2C3	4.00		.31	.89	8.00				3	30	34						
42.0	48.0	35477	6.0	5.9	2C3	3.90	40	.19	1.12	6.00				2	29	31						
48.0	53.2	35478	5.2	5.0	2D3	4.20		1.96	4.38	16.00				1	30	32						
53.2	59.0	35479	5.8	5.8	2C09	3.30	21	1.08	1.30	36.00				3	12	16						
59.0	64.0	35480	5.0	5.0	2C09	3.50		.06	.48	8.00					25	26						
64.0	70.0	35481	6.0	5.3	2D0	3.70	21	.02	.18	6.00				2	26	28						
70.0	76.0	35482	6.0	6.0	2C0	3.50		1.50	4.24	16.00				2	18	20						
76.0	81.0	35483	5.0	5.0	2E10	4.00		.10	.99	2.00					30	31						
81.0	86.0	35484	5.0	5.0	2E10	3.90	40	.25	.99	8.00				2	28	30						
86.0	93.0	35485	7.0	7.0	2E10	4.00		.63	2.04	8.00					33	34						
93.0	99.0	35486	6.0	6.0	2E10	3.90		.71	1.88	10.00					29	30						
99.0	105.0	35487	6.0	6.0	2CE	3.50	21	2.09	3.72	26.00				1	21	22						
105.0	111.5	35488	6.5	6.5	2CE	4.00		.10	.78	16.00				1	29	30						
111.5	116.0	35489	4.5	4.5	2C3	4.00		.05	.73	14.00				1	30	31						
116.0	122.0	35490	6.0	6.0	2C3	4.00	40	.07	1.21	16.00					30	31						
122.0	127.5	35491	5.5	5.5	2C3	4.10		.06	2.49	8.00					32	33						
127.5	132.5	35492	5.0	5.0	2C3	4.10		.04	2.46	4.00				2	30	33						
132.5	137.5	35493	5.0	5.0	2C3	3.90		.87	2.48	12.00				1	27	29						

START.

DDH: 86F-17

-----DEPTHS-----							-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP		CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %	S.G. W.R.	
137.5	143.0	35494	5.5	5.5 2C3	3.90		40	.32	2.33	8.00				1	27	28						
143.0	146.8	35495	3.8	3.8 2C3	4.10			.03	.41	4.00				1	32	34						
146.8	152.0	35496	5.2	5.2 2C3	4.00			.05	1.43	4.00				1	29	31						
152.0	156.5	35497	4.5	4.5 2C3	3.90		40	.28	2.07	6.00					27	28						
156.5	160.0	35498	3.5	3.5 2E1	3.90			.08	2.65	4.00					25	26						
160.0	164.0	35499	4.0	4.0 2E14	4.00			2.25	4.22	10.00				1	23	24						
164.0	168.7	35500	4.7	4.7 2D354	3.90			5.68	6.68	26.00				3	15	18						

↓ continued
on previous page.

DDH: 86F-18

---DEPTHS---							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
14.0	18.4	35104	4.4	4.4	2E18	3.90		.18	1.32	4.00		.21	4	27	32						
18.4	22.8	35105	4.4	4.4	1H4*	3.30		1.74	.48	25.00		.89	5	14	20						
22.8	29.0	35106	6.2	5.8	2E18	3.90	40	.19	.70	8.00		.24	5	28	34						
29.0	35.0	35107	6.0	6.0	2E18	4.00		.58	.71	6.00		.10	2	32	34						
35.0	39.8	35108	4.8	4.8	2A34	3.40		3.20	6.01	28.00		.27	4	14	19						
39.8	42.6	35109	2.8	2.8	2D7	3.30	33	3.14	6.05	32.00		.58	15	4	20						
42.6	46.0	35110	3.4	3.4	2C7	3.40		.50	.20	17.00		.51	16	6	23						
46.0	50.3	35111	4.3	4.3	1D4	3.10	Waste	1.28	.07	38.00		.99	3	4	8						
50.3	55.6	35112	5.3	4.4	10Q9	3.10		.29	.09	12.00		.65	2	14	16						
55.6	60.6	35113	5.0	5.0	2E18	3.60		.90	2.32	40.00		.38	5	18	24						
60.6	65.6	35114	5.0	5.0	2E18	3.90	40	.29	1.15	30.00		.10	1	29	30						
65.6	70.6	35115	5.0	5.0	2E18	3.90		.08	1.15	6.00		.07	2	30	32						
70.6	75.6	35116	5.0	5.0	2E18	3.80		.05	.69	6.00		.10	6	29	35						
75.6	80.6	35117	5.0	5.0	2E18	3.80		.56	.84	16.00		.07	2	29	31						
80.6	85.6	35118	5.0	5.0	2E18	4.10	40	.22	1.03	4.00		.07	1	32	34						
85.6	90.6	35119	5.0	5.0	2E18	3.70		.23	1.01	6.00		.21	1	27	28						
90.6	94.6	35120	4.0	4.0	2E18	3.80		.19	1.83	4.00		.14	1	29	30						
94.6	100.1	35121	5.5	5.5	2E18	4.20		.12	.72	6.00		.17	1	31	32						
100.1	104.0	35122	3.9	3.9	2E18	4.10	40	.06	.18	4.00		.14		34	34						
104.0	108.5	35123	4.5	4.5	2E18	4.00		.53	.28	14.00		.24		36	36						
108.5	113.8	35124	5.3	5.3	2E18	4.00		1.09	.46	20.00		.21		26	27						
113.8	118.0	35125	4.2	3.0	2E18	4.20		.17	.50	8.00		.21	1	37	38						
118.0	123.0	35126	5.0	5.0	2E18	4.50	40	.44	1.71	6.00		.07	5	30	35						
123.0	128.0	35127	5.0	5.0	2E18	3.80		.43	.86	4.00			6	26	32						
128.0	132.1	35128	4.1	4.1	2E18	3.90		.06	1.29	6.00			9	28	38						
132.1	135.0	35129	2.9	2.9	2E18	4.40		.09	.30	8.00		.10	7	34	41						
135.0	139.8	35130	4.8	4.8	2E1	4.00		.32	.91	10.00		.17	2	30	33						
139.8	144.0	35131	4.2	4.2	2E1	4.10	40	.39	1.68	8.00		.17	1	33	35						
144.0	148.5	35132	4.5	.0	2E1	4.50		.24	1.98	4.00		.10	3	35	39						
148.5	152.0	35133	3.5	.0	2E1	4.40		1.13	2.58	4.00		.07	3	34	37						
152.0	156.0	35134	4.0	4.0	2E14	4.20		1.80	4.14	6.00		.07	1	29	31						
156.0	160.0	35135	4.0	4.0	2E1	4.00	40	.40	1.80	4.00		.10	1	30	31						
160.0	165.2	35136	5.2	5.2	2E1	4.10		1.06	2.57	8.00		.17	1	28	30						
165.2	167.6	35137	2.4	2.4	2D0	3.90		2.09	6.67	20.00		.24	2	20	22						
167.6	171.0	35138	3.4	3.4	2D4	3.90	50	3.45	8.19	28.00		.24	3	20	23						
171.0	174.5	35139	3.5	3.5	2E4	4.90		7.01	19.30	58.00		.31	3	27	30						
202.0	206.7	35140	4.7	4.7	2D0	3.00		2.19	3.63	52.00		.51	2	2	4						
174.5	178.2	35422	3.7	3.7	2E4	5.00		4.10	9.31	32.00			1	36	37						
178.2	183.6	35423	5.4	2.9	1D49	2.90		.80	.93	12.00			2	3	5						
183.6	190.0	35424	6.4	6.4	2D0	2.90	21	1.46	3.56	24.00			4	3	7						
190.0	195.3	35425	5.3	5.3	2D0	3.10		1.11	3.59	20.00			6	3	10						
195.3	199.7	35426	4.4	4.4	10Q9	3.00		3.63	5.74	80.00			6	1	8						
199.7	202.0	35427	2.3	2.3	2D0	2.90	21	1.00	4.26	26.00			1	1	3						
206.7	211.1	35428	4.4	4.4	2A0	2.90		1.62	2.36	22.00			2	2	4						
211.1	215.4	35429	4.3	4.3	2A4	3.10		3.60	7.39	74.00			4	6	11						
215.4	220.1	35430	4.7	4.7	2A4	3.10		2.79	5.76	40.00			2	5	8						
220.1	225.1	35431	5.0	5.0	2A4	3.00		1.09	3.76	18.00			1	5	6						
225.1	229.1	35432	4.0	4.0	2D5	3.10	21	1.47	4.87	30.00			1	4	5						
229.1	234.0	35433	4.9	4.9	2D5	3.00		1.07	4.20	16.00			1	3	5						
234.0	238.2	35434	4.2	4.2	2D5	3.00		1.71	5.05	24.00			2	2	4						
238.2	243.2	35435	5.0	5.0	2D5	3.00		2.49	6.82	36.00			2	1	4						

DDH: 86F-18

-----DEPTHS-----				-----ASSAYS-----																	
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %	S.G. W.R.	
243.2	247.7	35436	4.5	4.5	2D5	3.10	21	4.66	3.90	155.00				1	3	5					
247.7	251.9	35437	4.2	4.2	2D5	3.20		3.40	3.98	74.00				3	4	8					
251.9	256.1	35438	4.2	4.2	2C0	3.20		.34	1.12	14.00				2	4	7					
256.1	260.3	35439	4.2	4.2	2C0	3.00	21	1.25	.21	24.00				3	3	7					
260.3	265.0	35440	4.7	4.7	2C0	2.90		1.57	.56	54.00				2	3	6					

DDH: 86F-19

							-----ASSAYS-----														
----DEPTHS----		SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %	S.G. W.R.	
FROM	TO																				
100.9	105.0	35441	4.1	4.1	2D5	3.50		.62	4.35	10.00			2	17	20						
105.0	111.7	35442	6.7	6.7	2C35	3.80	40	.18	1.08	6.00			1	28	30						
111.7	117.0	35443	5.3	5.3	2E810	4.20		.12	.75	6.00			6	30	36						
117.0	122.6	35444	5.6	5.6	2E180	4.00		.05	.99	4.00			4	30	34						
122.6	127.0	35445	4.4	4.4	2C38	3.90	40	.04	1.76	4.00			7	22	29						
127.0	132.3	35446	5.3	5.3	2C38	3.90		.35	2.16	4.00			7	25	33						
132.3	137.0	35447	4.7	4.7	2C38	4.00		.70	1.71	6.00			6	25	31						
137.0	141.0	35448	4.0	4.0	2C38	3.90	40	1.00	1.99	14.00			8	26	34						
141.0	145.2	35449	4.2	4.2	2C38	3.60		2.77	1.21	56.00			4	19	24						
145.2	151.1	35450	5.9	5.9	2E81	4.10		.47	2.15	10.00			6	29	36						
151.1	154.4	35451	3.3	3.3	2E41	4.20		5.63	10.00	16.00			2	27	30						
154.4	158.3	35452	3.9	3.9	2E41	4.20	50	4.26	9.46	12.00			2	26	29						
158.3	164.0	35453	5.7	5.7	2D354	3.60		2.82	8.13	18.00			2	18	20						
164.0	170.5	35454	6.5	6.5	2D354	3.50	50	2.62	9.46	22.00			3	17	21						
170.5	175.7	35455	5.2	5.1	2E4	4.80		3.33	8.29	22.00			3	34	38						
175.7	178.6	35456	2.9	2.9	2A34	3.90		4.03	11.90	38.00			2	20	23						
178.6	183.5	35457	4.9	4.9	2A0	2.90		1.41	1.73	20.00			2	2	5						
183.5	188.9	35458	5.4	4.7	2A0	3.00	21	1.05	2.19	16.00			4	8	12						
188.9	192.0	35459	3.1	3.1	2A0	2.90		.55	2.26	12.00			1	18	20						
192.0	199.3	35460	7.3	7.3	2D5	3.10		.97	3.66	16.00			2	8	11						
199.3	204.0	35461	4.7	4.7	2C0	2.80		.16	.17	14.00			2	3	5						
204.0	209.0	35462	5.0	4.9	2C0	3.00	21	.07	.12	6.00			3	4	8						
209.0	214.0	35463	5.0	4.7	2C0	3.00		.25	.71	10.00			3	4	7						
214.0	224.0	35464	10.0	10.0	1D419	2.80		.60	.39	14.00			2	1	3						
224.0	233.5	35465	9.5	9.5	1D419	2.80		.22	.31	6.00			2	2	4						
233.5	243.0	35466	9.5	9.5	1D419	2.90		.24	.22	12.00			2	1	4						
243.0	251.0	35467	8.0	8.0	1D29	2.80		.10	.19	2.00			2	1	3						
251.0	259.0	35468	8.0	7.7	1D419	2.80		.38	.73	8.00			2	1	4						
259.0	267.0	35469	8.0	8.0	1D419	2.80		.36	.83	8.00			3	2	6						

DDH: 86F-20

DEPTHS		SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	ASSAYS												S.G. W.R.	
FROM	TO					CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %		As %
11.0	21.8	10653	10.8	9.9 2E40	4.10	50	4.14	6.46	48.00				2	27	30				
21.8	27.0	10654	5.2	4.1 2E1	4.60		1.28	1.43	16.00				1	38	40				
27.0	30.5	10655	3.5	2.3 2E1	4.40	40	.19	.31	8.00				1	35	37				
30.5	36.5	10656	6.0	5.4 2A3	3.60		.29	.83	6.00					24	24				
36.5	41.5	10657	5.0	4.3 2A34	3.50	33	1.07	4.92	16.00				1	19	20				
41.5	44.6	10658	3.1	2.7 2C3	4.00	40	.87	1.90	14.00				1	31	32				
44.6	49.0	10659	4.4	4.2 2C3	4.20		1.07	2.08	6.00				7	29	37				
49.0	54.5	10660	5.5	5.2 2E4	4.40		1.80	4.19	8.00				7	30	38				
54.5	59.5	10661	5.0	4.6 2E4	4.20	50	1.96	3.99	8.00				6	28	35				
59.5	64.0	10662	4.5	4.4 2E4	4.40		2.57	4.14	12.00				8	29	37				
64.0	68.5	10663	4.5	4.5 2E0	4.50		1.22	2.11	6.00				8	30	39				
68.5	72.7	10664	4.2	4.1 2E0	4.10		.07	1.64	4.00				6	31	37				
72.7	78.0	10665	5.3	5.1 2E0	4.20	50	.03	.67	2.00				2	34	37				
78.0	83.0	10666	5.0	4.9 2E0	4.20		.21	1.89	4.00				4	32	36				
83.0	87.5	10667	4.5	4.3 2E0	4.20		.24	.63	6.00				1	34	36				
87.5	93.0	10668	5.5	5.4 2A34	3.70		2.21	5.23	8.00				1	24	26				
93.0	97.2	10669	4.2	4.1 2A3	3.80	50	.36	2.15	4.00				2	28	30				
97.2	101.8	10670	4.6	4.3 2A34	3.30		2.96	5.78	36.00				2	11	14				
101.8	106.8	10671	5.0	4.8 2A34	3.70		1.23	3.22	14.00				1	33	35				
106.8	113.0	10672	6.2	5.1 2E1	4.00		.43	3.37	6.00				5	29	34				
113.0	117.0	10673	4.0	3.2 2E1	3.80	40	.14	1.72	4.00				5	28	33				
117.0	121.2	10674	4.2	2.5 2E81	3.80		.06	1.01	6.00				5	26	31				
121.2	126.5	10675	5.3	5.1 2E81	3.80		.09	1.63	2.00				4	28	32				
126.5	131.8	10676	5.3	5.2 2E81	4.00		.06	1.74	4.00				6	30	36				
131.8	136.8	10677	5.0	4.9 2C3	3.60	40	.10	.83	4.00				5	23	28				
136.8	141.0	10678	4.2	3.4 2C3	3.90		.11	1.65	4.00				7	26	33				
141.0	145.5	10679	4.5	4.4 2C3	4.10		.20	2.38	10.00				7	28	36				
145.5	150.5	10680	5.0	4.7 2D3	3.90	40	1.86	2.89	38.00				5	26	31				
150.5	155.0	10681	4.5	3.2 2E1	4.40		.30	1.27	6.00				4	35	39				
155.0	158.6	10682	3.6	3.5 2E1	4.30		.05	1.18	2.00				3	36	40				
158.6	162.0	10683	3.4	3.2 2E4	4.20	50	.35	1.24	2.00				3	35	38				
162.0	167.5	10684	5.5	5.3 2E4	4.50		3.54	5.94	8.00				3	34	38				
167.5	173.0	10685	5.5	4.8 2A4	4.50		2.86	6.41	8.00				3	34	37				
173.0	179.0	10686	6.0	3.8 2A4	3.70	21	3.59	8.93	18.00				2	20	22				
179.0	184.1	10687	5.1	4.2 2A4	3.60		6.27	12.50	44.00				3	13	16				
184.1	190.0	10688	5.9	4.9 2A4	4.00		4.58	11.20	24.00				1	26	28				
190.0	194.7	10689	4.7	3.5 2C0	3.00	21	.71	1.60	40.00				2	8	11				
194.7	200.8	10690	6.1	4.7 2C0	3.10		.50	1.71	8.00				3	9	13				
200.8	206.7	10691	5.9	5.1 2C0	3.10		.90	2.78	16.00				2	11	14				
206.7	211.0	10692	4.3	4.2 2C0	2.80	21	.96	1.83	14.00				2	2	4				
211.0	216.0	10693	5.0	3.3 2C0	2.90		.13	.18	4.00				3	5	8				

DDH: 86F-21

-----ASSAYS-----

---DEPTHS---		SAMPLE INT. REC. ROCK	S.G.	CU	Pb	Zn	Ag(AA)	Ag(FA)	Au(FA)	Po	Py	TOT	BAO	Hg	Mn	As	Ba	S.G.
FROM	TO																	
90.5	95.0	10610	4.5	3.9	2E1	3.90		.76	2.07	4.00		1	28	29				
219.0	231.3	10611	12.3	10.2	2D5	2.90		1.92	5.05	32.00		4	10	15				
108.5	114.0	10612	5.5	4.9	BXA	3.70		3.95	7.10	22.00		2	20	22				
43.0	47.0	10613	4.0	3.8	2C3	3.20		.71	.95	8.00		2	15	17				
52.3	62.2	10614	9.9	7.6	1D4	3.00		.83	.13	38.00		3	2	5				
151.2	155.2	10615	4.0	3.6	2E18	4.10		.67	1.97	6.00		4	28	32				
280.7	289.0	10616	8.3	7.5	1D419	2.80		1.03	1.92	8.00		2	1	4				
10.0	16.0	34751	6.0	5.4	2C38	3.90		.48	1.38	10.00		1	30	32				
16.0	21.0	34752	5.0	4.7	2C38	4.10	40	.75	1.02	8.00		4	30	35				
21.0	26.0	34753	5.0	4.7	2C38	4.10	40	.25	1.58	10.00		6	28	35				
26.0	31.0	34754	5.0	4.8	2C38	4.20		.37	1.19	4.00		4	30	35				
31.0	36.0	34755	5.0	4.9	2C38	4.30		.06	.56	4.00		4	35	39				
36.0	41.0	34756	5.0	4.7	2C38	4.40	40	.49	.37	6.00		2	37	40				
41.0	43.0	34757	2.0	1.8	2C38	3.70	40	.87	1.03	4.00			28	29				
47.0	52.3	34758	5.3	5.3	2A0	3.70		.70	1.22	12.00		2	22	25				
62.2	67.0	34759	4.8	4.6	2C3	3.70		1.11	2.09	14.00		2	23	26				
67.0	71.5	34760	4.5	4.2	2C3	3.90	40	.79	1.34	8.00		1	25	27				
71.5	75.5	34761	4.0	3.8	2C3	4.00		.15	.40	4.00			30	31				
75.5	80.5	34762	5.0	4.7	2C3	3.90		.04	1.42	2.00		1	30	32				
80.5	85.5	34763	5.0	4.9	2E81	4.50	40	.14	1.15	2.00		6	30	37				
85.5	90.5	34764	5.0	4.8	2E81	3.80	40	.63	.74	4.00		7	28	36				
95.0	99.5	34765	4.5	4.3	2E1	3.70		.70	1.08	6.00		1	30	31				
99.5	104.0	34766	4.5	4.2	2E1	4.60	40	1.03	.55	14.00			35	35				
104.0	108.5	34767	4.5	4.4	2E1	3.90	40	3.09	.31	34.00			29	30				
114.0	121.7	34768	7.7	7.2	2A3	3.90	21	.96	1.36	12.00		1	24	25				
121.7	126.7	34769	5.0	4.7	2C38	4.10		.50	1.42	2.00		3	32	35				
126.7	131.7	34770	5.0	4.9	2C38	3.90		.34	1.36	2.00		7	24	31				
131.7	136.3	34771	4.6	4.5	2C38	4.10	40	.12	.37	4.00		5	31	36				
136.3	140.5	34772	4.2	3.9	2C38	4.00		.15	1.33	2.00		1	31	33				
140.5	145.5	34773	5.0	4.6	2C38	4.00		.10	1.81	2.00		2	30	32				
145.5	151.2	34774	5.7	5.5	2C38	4.20	40	.22	1.38	2.00		3	27	30				
155.2	161.0	34775	5.8	5.3	2D3	4.20	40	.59	1.80	4.00		2	27	30				
161.0	166.0	34776	5.0	4.8	2C3	3.60		.13	2.21	4.00		1	24	26				
166.0	174.0	34777	8.0	7.1	2C3	4.00	50	2.50	6.00	8.00		2	24	27				
174.0	177.0	34778	3.0	2.1	2D5	4.20		6.79	6.16	74.00		2	34	36				
177.0	182.0	34779	5.0	4.4	2D5	3.80		1.07	3.20	30.00		1	18	20				
182.0	186.0	34780	4.0	3.5	2D5	3.40	21	2.48	5.88	24.00		3	12	16				
186.0	190.0	34781	4.0	3.3	2C5	3.30		1.57	2.10	36.00		1	5	7				
190.0	194.5	34782	4.5	4.2	2D5	2.90		1.67	3.07	22.00		2	3	6				
194.5	200.0	34783	5.5	4.0	2D5	2.90		1.19	3.02	20.00		3	6	10				
200.0	205.0	34784	5.0	4.8	2C5	3.10	21	1.32	2.05	18.00		3	8	12				
205.0	210.0	34785	5.0	4.9	2C5	3.20		1.04	1.72	16.00		3	9	13				
210.0	215.0	34786	5.0	4.7	2C5	3.10		2.16	1.55	42.00		2	3	5				
215.0	219.0	34787	4.0	3.5	2A4	3.30	21	5.00	7.42	44.00		3	15	19				
231.3	237.0	34788	5.7	5.4	2D5	2.80		1.05	3.65	26.00		2	2	5				
237.0	242.0	34789	5.0	4.4	2D5	2.80		.85	3.46	20.00		1	1	2				
242.0	247.0	34790	5.0	4.6	2C5	2.80	21	.71	2.82	16.00		1	2	3				
247.0	252.0	34791	5.0	4.9	2D5	2.90		2.00	3.96	36.00		2	3	5				
252.0	257.0	34792	5.0	4.7	2D5	2.90		.32	3.55	24.00		1	4	6				
257.0	264.0	34793	7.0	6.3	2D5	2.90	21	1.52	4.43	26.00		2	3	5				
264.0	269.0	34794	5.0	4.1	2C5	2.90		.84	3.13	22.00		1	2	4				

add
bally

Separate
Waste

BXA

DDH: 86F-21

-----DEPTHS-----							-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP		CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %	S.G. W.R.	
269.0	272.0	34795	3.0	2.8	2D5	2.90	21 1.63	3.47	24.00				2	3	6							
272.0	277.5	34796	5.5	4.6	2C5	2.90	.27	.28	10.00				2	3	6							
277.5	280.7	34797	3.2	2.9	1D419	2.90	.62	1.20	26.00				3	3	6							
289.0	296.5	34798	7.5	7.1	1D419	2.90	2.11	.97	22.00				2	3	6							
296.5	299.0	34799	2.5	2.3	1D419	3.00	3.45	1.85	40.00				4	7	11							

DDH: 86F-22

DEPTH FROM	DEPTH TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	ASSAYS											S.G. W.R.					
						CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe %	BAO %	Hg %		Mn %	As %	Ba %		
209.6	214.4	10601	4.8	4.5	2D59	2.90		1.03	4.21	24.00			2	2	5							
214.4	218.7	10602	4.3	3.9	2C59	3.10		.33	2.41	10.00			6	9	16							
218.7	223.7	10603	5.0	4.8	2C59	3.10		1.07	2.07	22.00			6	8	14							
223.7	228.5	10604	4.8	4.8	2C59	2.90	Z1	.84	1.63	16.00			1	2	4							
236.5	240.3	10605	3.8	3.3	1CD4	2.90		.03	.03	4.00			3		4							
240.3	244.7	10606	4.4	4.2	1CD4	2.90		.02	.12	2.00			5	2	7							
244.7	248.8	10607	4.1	3.8	1CD4	2.80		.06	.05	4.00			3	1	4							
254.5	258.0	10608	3.5	3.2	2A0	2.90		.68	2.91	16.00			4	4	8							
258.0	262.0	10609	4.0	3.8	2A0	2.90		.75	2.23	16.00			3	1	5							
266.0	269.6	10617	3.6	3.4	2D5	3.70	Z1	3.77	4.11	34.00			3	20	23							
262.0	267.0	10618	5.0	4.8	2C0	2.70		.53	1.65	8.00			2	2	4							
267.0	272.0	10619	5.0	4.7	2C0	2.80		1.11	1.24	12.00			2	3	6							
272.0	278.5	10620	6.5	5.9	2A70	2.90	Z1	.41	1.30	8.00			3	3	7							
278.5	284.0	10621	5.5	5.4	2A70	2.80		.80	1.48	16.00			4		5							
284.0	290.7	10622	6.7	6.4	2A70	2.90		.52	1.55	12.00			3	1	5							
290.7	297.0	10623	6.3	5.9	2A70	2.80	Z1	.66	2.31	18.00			3	2	5							
297.0	302.0	10624	5.0	4.8	2DJ4	3.90		33.60	2.43	276.00			2	1	4							
302.0	306.0	10625	4.0	3.7	2L14	2.80	Waste	.89	1.59	17.00			2	1	3							
228.5	232.6	10626	4.1	3.8	2C0	2.90		.71	.72	11.00			2	2	5							
232.6	236.5	10627	3.9	3.1	1CD4	2.90	Waste	.03	.10				3	1	4							
248.8	254.5	10628	5.7	5.6	2C0	2.90	Z1	.83	1.07	10.00			2	2	4							
104.3	108.2	10629	3.9	3.7	1H0	3.00		1.98	3.28	44.00			2	3	5							
108.2	110.4	10630	2.2	2.1	2G74	4.30	80	4.27	6.49	84.00			20	10	30							
110.4	115.0	10631	4.6	3.9	1H0	3.20		2.82	2.26	44.00			7	10	18							
115.0	117.5	10632	2.5	2.4	2G7	4.00		3.73	6.00	68.00			12	16	28							
117.5	123.0	10633	5.5	5.3	1H0	4.40	80	2.46	3.80	46.00			8	12	20							
123.0	131.2	10634	8.2	7.9	1H0	3.00		1.37	.95	18.00			5	3	9							
131.2	135.0	10635	3.8	3.7	2G74	4.30	60	5.74	7.63	64.00			4	17	22							
135.0	141.5	10636	6.5	6.1	2E4	4.50		3.44	2.90	48.00			6	29	35							
141.5	146.8	10637	5.3	5.0	2E0	4.50	50	1.33	1.15	14.00			5	28	34							
146.8	152.2	10638	5.4	5.2	2E0	4.60		1.13	.40	24.00			10	32	42							
152.2	156.5	10639	4.3	4.2	2E4#	4.50		5.11	5.51	22.00			12	26	38							
156.5	160.8	10640	4.3	4.1	2E4#	4.40	50	4.12	4.12	26.00			13	24	37							
160.8	165.2	10641	4.4	4.3	2E#	4.30		.45	.20	6.00			9	31	41							
165.2	170.1	10642	4.9	4.7	2E84	4.70		2.23	2.69	30.00			3	37	41							
170.1	174.5	10643	4.4	4.2	2E80	4.70		2.06	1.62	50.00			7	34	41							
174.5	179.0	10644	4.5	4.5	2E80	4.40	40	1.89	.79	36.00			10	30	41							
179.0	183.3	10645	4.3	4.1	2E84	4.40		2.83	2.10	48.00			12	27	40							
183.3	188.7	10646	5.4	5.0	2E84	4.40		2.38	3.17	34.00			14	28	42							
188.7	192.0	10647	3.3	2.9	2E4	4.80	40	3.18	4.56	28.00			2	35	38							
192.0	196.0	10648	4.0	3.6	2E0	4.10		.85	2.39	18.00			4	29	33							
196.0	199.5	10649	3.5	2.5	2E4	4.60		4.18	5.47	32.00			3	32	36							
199.5	203.7	10650	4.2	3.6	2E4	4.70	50	2.57	5.33	24.00			2	35	38							
203.7	206.0	10652	2.3	1.8	2E4	4.70		5.21	5.96	32.00				36	37							

DDH: 86F-23

---DEPTHS---		SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													
FROM	TO					CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %
106.0	111.0	04967	5.0	4.9 2E4	4.10	60	3.58	6.30	57.00				2	25	27				
111.0	116.0	04968	5.0	4.7 2E4	4.70		9.96	8.75	167.00				4	22	26				
116.0	122.5	04969	6.5	4.4 2E4	3.70	50	2.66	10.90	19.00				3	14	17				
122.5	127.0	04970	4.5	4.3 2E4	3.90		5.02	10.10	55.00				4	24	29				
127.0	132.0	04971	5.0	4.9 2A3	3.80		.93	1.09	11.00				2	24	27				
132.0	136.5	04972	4.5	4.1 2E0	4.60	23	.25	.36	8.00				2	40	42				
136.5	140.0	04973	3.5	3.5 2E0	4.70		.64	.86	8.00				1	40	41				
140.0	144.5	04974	4.5	4.1 2A34	3.90		1.32	4.99	9.00				1	23	24				
144.5	148.7	04975	4.2	4.0 2A34	3.80		2.10	6.11	19.00				1	21	23				
148.7	152.7	04976	4.0	3.8 2A3	3.80	23	.48	1.80	11.00					30	31				
152.7	156.7	04977	4.0	3.9 2A3	3.90		.50	1.30	9.00				1	29	30				
156.7	161.5	04978	4.8	4.5 2E81	4.20	40	.57	2.11	6.00				6	30	36				
161.5	166.5	04979	5.0	4.3 2E81	4.20		1.31	2.36	8.00				8	30	39				
166.5	170.8	04980	4.3	3.0 2E81	4.20	40	.71	1.89	8.00				7	28	35				
170.8	177.0	04981	6.2	5.8 2E1	4.10		.08	.61	9.00					35	35				
177.0	183.0	04982	6.0	4.2 2E1	3.80		.59	.72	9.00				1	28	29				
189.0	193.2	04983	4.2	3.8 2C35	3.40		.90	2.57	10.00				5	18	24				
183.0	189.0	04984	6.0	5.6 2D34	3.40	21	3.34	8.62	20.00				2	14	17				
193.2	198.0	04985	4.8	4.5 2C35	3.60		.38	.79	20.00				9	21	30				
198.0	204.0	04986	6.0	5.7 2D45	3.80		3.38	5.94	20.00				5	7	13				

DDH: 86F-25

-----							-----ASSAYS-----															
---DEPTHS---	SAMPLE	INT.	REC.	ROCK	S.G.		CU	Pb	Zn	Ag(AA)	Ag(FA)	Au(FA)	Po	Py	TOT	BAO	Hg	Mn	As	Ba	S.G.	
FROM	TO	NO.		UNIT	PULP		%	%	%	g/mT	g/mT	g/mT	%	%	Fe	%	%	%	%	%	W.R.	
167.5	170.0	10694	2.5	2.4	2D0	3.10		2.02	3.39	36.00				5	9	15						
170.0	175.5	10695	5.5	3.3	1D4	2.80		.47	.27	10.00				2	2	5						
175.5	181.0	10696	5.5	3.1	2LE34	3.70		4.31	3.97	74.00				11	15	26						
181.0	185.0	10697	4.0	1.7	2LE34	4.30	80	5.30	4.95	84.00				14	21	36						
185.0	189.7	10698	4.7	2.4	2LE34	3.50		2.97	2.38	44.00				8	17	25						
189.7	195.7	10699	6.0	5.9	2G4	4.10		5.00	5.01	72.00				2	21	23						
195.7	200.0	10700	4.3	4.1	2E4L	3.60		.87	1.01	30.00				5	23	28						
200.0	207.8	10701	7.8	7.4	1H4	2.90		.72	.31	38.00				7	4	12						
207.8	212.5	10702	4.7	4.4	2E0	4.10		2.44	1.23	32.00				1	36	38						
212.5	217.6	10703	5.1	5.0	2E4	4.60	50	1.69	2.40	22.00				1	38	40						
217.6	221.6	10704	4.0	3.7	2E4	4.70		2.57	3.91	22.00					41	42						
221.6	226.0	10705	4.4	3.9	2E4	4.30	50	4.78	3.40	28.00				1	30	32						
226.0	232.5	10706	6.5	5.7	2E4	4.60		3.17	3.17	32.00				4	36	40						
232.5	239.8	10707	7.3	6.8	2C3	4.00	40	2.18	.17	34.00					33	33						
239.8	244.6	10708	4.8	4.7	2E0	4.60		1.54	.86	24.00				2	40	42						
244.6	250.7	10709	6.1	5.9	2E0	4.80		1.47	.75	20.00				1	39	41						
250.7	258.0	10710	7.3	6.9	2E84	4.60	50	2.93	2.30	44.00				4	36	40						
258.0	264.0	10711	6.0	5.8	2E84	4.50		3.15	3.95	36.00				5	32	38						
264.0	268.8	10712	4.8	4.4	2E8	4.40		1.14	2.78	14.00				7	31	39						
268.8	273.0	10713	4.2	3.5	2E0	4.40		.92	1.12	8.00				1	38	39						
273.0	278.0	10714	5.0	4.8	2E4	4.80		5.35	8.18	44.00				1	36	37						
278.0	282.0	10715	4.0	4.0	2E0	4.50	50	.13	.14	6.00					39	40						
282.0	286.7	10716	4.7	2.1	2E0	4.50		2.06	1.88	16.00				1	37	39						
286.7	290.0	10717	3.3	2.3	2E8	4.50		1.63	1.95	14.00				6	34	41						
290.0	295.0	10718	5.0	4.2	2E8	4.00		1.46	2.12	12.00				2	31	34						
295.0	299.0	10719	4.0	3.9	2E84	4.50	50	2.35	5.33	16.00				6	32	39						
299.0	303.0	10720	4.0	3.8	2E8	4.60		.55	.66	6.00				6	37	44						
303.0	306.5	10721	3.5	2.2	2E8	4.60		1.45	2.24	12.00				8	33	41						
306.5	310.0	10722	3.5	3.2	2E4	4.60		2.10	3.00	24.00				5	35	41						
310.0	315.0	10723	5.0	3.9	2E4	4.70	50	3.00	6.15	20.00				4	33	37						
315.0	319.0	10724	4.0	3.4	2E4	4.50		2.70	5.38	20.00				1	36	38						
319.0	324.0	10725	5.0	3.6	2E4	4.80		3.46	5.21	20.00					37	38						
324.0	330.0	10726	6.0	3.7	2E4	4.70		2.00	3.48	14.00				1	40	41						
330.0	335.0	10727	5.0	4.1	2E4	4.60	50	4.90	9.35	22.00				1	33	35						
335.0	339.0	10728	4.0	3.7	2E4	4.60		3.45	6.85	16.00				2	32	34						
339.0	343.5	10729	4.5	4.2	2E4	4.40		4.16	8.59	20.00				2	32	35						
343.5	348.0	10730	4.5	2.3	2C5	3.30		1.27	1.87	18.00				6	13	20						
348.0	355.0	10731	7.0	6.8	2C5	3.00	21	1.25	2.73	24.00				2	4	6						
355.0	361.3	10732	6.3	5.8	2D5	3.00		2.11	2.06	32.00				2	2	4						
361.3	364.0	10733	2.7	2.6	2C05	3.30		.25	.43	8.00				10	13	24						
364.0	367.0	10734	3.0	2.9	2D75	3.60		1.63	4.34	24.00				13	15	28						
367.0	374.0	10735	7.0	6.8	2C5	3.10	21	.40	2.09	10.00				3	11	15						
374.0	378.5	10736	4.5	4.5	2C0	2.80		.68	1.44	16.00				1	4	6						
378.5	383.0	10737	4.5	4.4	2C0	2.90		.81	2.12	16.00				3	3	7						

DDH: 87F-01

---DEPTHS---							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %	S.G. W.R.	
264.0	268.5	09502	4.5	4.5 2H	70	1.98	3.98	32.00						23 17 40							
268.5	271.4	09503	2.9	2.9 2E4		4.02	7.37	56.00						4 33 37							
271.4	275.0	09504	3.6	3.6 2E4	50	6.36	7.66	90.00						6 29 36							
275.0	277.4	09505	2.4	2.4 BXA		7.30	7.80	102.00						15 18 34							
277.4	280.5	09506	3.1	3.1 2E4		6.52	6.96	78.00						4 34 38							
280.5	284.2	09507	3.7	3.7 2H	70	1.90	3.26	37.00						17 25 42							
284.2	288.7	09508	4.5	4.5 2H		2.81	4.96	47.00						32 13 45							
288.7	293.4	09509	4.7	4.7 2E46		5.95	6.35	88.00						4 32 37							
293.4	297.6	09510	4.2	4.2 2E4		5.14	5.80	64.00						2 37 39							
297.6	302.2	09511	4.6	4.6 2E4	50	5.21	7.77	66.00						2 36 38							
302.2	303.6	09512	1.4	1.4 2E43B		5.88	6.65	76.00						7 24 32							
303.6	308.8	09513	5.2	4.4 2E46		4.60	5.47	62.00						6 26 33							
308.8	312.7	09514	3.9	3.9 2E46		5.10	5.47	68.00						7 24 31							
312.7	319.6	09515	6.9	6.9 2F4	50	6.18	6.15	88.00						6 27 33							
319.6	324.3	09516	4.7	4.7 2F4		5.96	6.14	91.00						4 30 35							
324.3	328.5	09517	4.2	4.2 2E4		5.47	6.31	89.00						5 30 36							
328.5	330.3	09518	1.8	1.8 2E4		4.94	6.92	78.00						10 23 33							

66.3
 7.96, 6.05, 70.91

h
 z
 n
 mmm
 n

DDH: 87F-02

---DEPTHS---				SAMPLE INT. REC. ROCK				-----ASSAYS-----																	
FROM	TO	NO.	UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %	S.G. W.R.						
191.1	195.3	09532	2C2	3.10		.13	.18	10.00				4	12	16											
195.3	197.0	09533	2D4	3.30	33	1.50	7.48	26.00				2	14	16											
197.0	201.0	09534	2G42	4.50	60	5.67	7.75	69.00				3	25	29											
201.0	203.9	09535	2G42	4.60		3.86	5.17	57.00				7	26	33											
203.9	207.0	09536	2EF4	4.70		6.23	5.69	95.00				5	27	32											
207.0	211.0	09537	2EF4	4.70		9.10	6.07	65.00				8	22	30											
211.0	216.0	09538	2E4	4.80	50	9.17	7.97	108.00				2	32	34											
216.0	222.1	09539	2E4	4.40		7.93	5.98	101.00				9	24	33											
222.1	224.8	09540	2H4	4.60		7.16	5.95	109.00				13	23	37											
224.8	229.2	09541	2G24	4.70	60	6.50	5.72	99.00				5	25	30											
229.2	233.3	09542	2G24	4.60		6.52	5.75	97.00				9	22	32											
233.3	238.0	09543	2H4	4.40		6.03	5.26	97.00				20	13	33											
238.0	242.7	09544	2H4	4.50	70	6.43	9.28	93.00				25	12	38											
242.7	247.4	09545	2H4	4.50		7.20	9.15	111.00				25	13	39											
247.4	251.4	09546	2CD	3.00		2.30	6.41	39.00				3	3	7											
251.4	255.6	09547	2CD	2.90		1.89	3.28	33.00				3	3	6											
255.6	259.5	09548	2CD	3.20	22	2.83	5.53	41.00				3	4	8											
259.5	264.3	09549	2CD	2.90		1.97	4.10	33.00				3	3	6											
264.3	268.2	09551	2CD	2.80		1.07	3.09	18.00				2	3	5											
268.2	272.4	09552	2A	2.70		.89	2.82	16.00				1	1	2											
272.4	276.4	09553	2A	2.80		.86	2.30	16.00				1	2	3											
276.4	281.2	09554	2A	2.90	22	1.61	3.21	22.00				4	3	8											
281.2	285.6	09555	2D	3.30		.06	3.49	6.00				4	10	15											
285.6	289.8	09556	2D4	3.20		1.17	11.70	22.00				5	6	11											
289.8	293.2	09557	2D4	3.60		3.90	21.60	59.00				8	7	16											
293.2	297.0	09558	2D4	3.50		6.41	13.20	97.00				7	10	18											
297.0	300.6	09559	2H4	4.40	22	10.60	13.10	143.00				25	10	36											
300.6	304.6	09560	2D4	3.40		5.67	12.10	81.00				8	8	17											
304.6	309.2	09561	2D4	3.40		3.48	19.10	54.00				7	6	14											
309.2	314.0	09562	2D4	2.90		1.69	12.30	29.00				1	7	9											
314.0	318.4	09563	2A4	2.90	22	1.73	5.40	27.00				1	1	3											
318.4	322.8	09564	2A4	2.80		2.16	6.83	37.00				1	1	2											
322.8	326.9	09565	2A4	2.90		2.27	6.51	33.00				2	3	5											
326.9	331.0	09566	2A4	2.90	22	1.58	7.19	27.00				2	3	5											
331.0	335.6	09567	2A4	2.90		1.44	7.77	37.00				3	2	5											
335.6	340.5	09568	2B4	2.50		1.80	7.61	37.00				4	3	8											
340.5	344.4	09569	2E	4.70		3.53	5.53	39.00				3	38	41											
344.4	349.5	09570	2E	4.70	50	3.41	2.96	28.00				2	40	42											
349.5	353.4	09571	2E	2.70		1.93	1.96	21.00				3	40	44											
353.4	360.0	09572	2E	4.70		1.71	2.32	15.00				2	39	41											
360.0	365.0	09573	2E	4.70	50	2.16	1.40	27.00				7	36	43											
365.0	369.0	09574	2E	4.10		3.07	5.93	45.00				15	19	34											
369.0	373.6	09575	2D	4.70		1.56	3.11	24.00				5	37	43											
373.6	379.4	09576	2D	2.40		1.48	3.41	32.00				5	9	15											
379.4	383.5	09577	2D5	2.30	21	1.03	1.91	26.00				5	5	11											

56.1'
6.464, 6.751

34.2'
1.397, 3.476

63.9'
3.239, 9.935

154.21'
4.00, 7.34, 59.26

DDH: 87F-03

-----DEPTHS-----							-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %	S.G. W.R.	
267.0	271.9	09519	4.9	4.9	2B	2.90		.23	.27	8.00					3	2	6					
271.9	276.0	09520	4.1	4.1	2D4	3.30	33	2.74	4.48	49.00					4	8	12					
276.0	279.6	09521	3.6	3.6	2D4	3.40		3.57	7.07	45.00					3	14	17					
279.6	282.0	09522	2.4	2.4	2C3	2.90		1.51	3.89	21.00					1	5	7					
282.0	287.0	09523	5.0	5.0	2A	2.80		1.01	1.97	23.00					1	7	8					
287.0	292.8	09524	5.8	5.8	2A	2.80	21	.83	1.74	19.00					3	3	7					
292.8	295.7	09525	2.9	2.9	2C3	2.80		.44	.40	11.00					4	5	9					
295.7	301.6	09526	5.9	5.9	1C14	2.80		.04	.08	2.00					2	1	3					
301.6	307.2	09527	5.6	5.6	1C14	2.80		.05	.09	2.00					3	2	5					
307.2	312.6	09528	5.4	5.4	2C3	3.00		.18	.25	4.00					3	7	10					
312.6	317.0	09529	4.4	4.4	1C14	2.80	21	.03	.12	2.00					4	1	5					
317.0	320.1	09530	3.1	3.1	1C14	2.40		.34	.13	6.00					4	3	8					
320.1	324.0	09531	3.9	2.9	2A	2.90		.52	1.09	14.00					3	3	6					

DDH: 87F-04

DEPTHS		SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	ASSAYS										S.G. W.R.		
FROM	TO								Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %		Ba %	
219.5	222.0	09578	2.5	2.5	2B	3.10	.16	.55	11.00				4	12	16						
222.0	226.1	09579	4.1	4.1	2D4	3.20	33	2.84	7.70	37.00			2	9	12						
226.1	231.0	09580	4.9	4.9	2F468	4.60	60	5.37	6.01	87.00			5	27	32						
231.0	236.0	09581	5.0	5.0	2F468	4.70		7.04	5.58	111.00			7	19	27						
236.0	241.0	09582	5.0	5.0	2F468	4.70		7.85	6.95	97.00			6	20	26						
241.0	246.0	09583	5.0	5.0	2F468	4.50		7.87	6.92	89.00			6	19	25						
246.0	251.0	09584	5.0	5.0	2F468	3.10		7.57	6.39	97.00			6	21	27						
251.0	254.6	09585	3.6	3.6	2F468	4.70	60	8.28	6.78	111.00			6	18	25						
254.6	258.5	09586	3.9	3.9	2F468	4.70		7.57	6.52	105.00			5	21	27						
258.5	262.0	09587	3.5	3.5	2H4	4.50		6.09	5.60	103.00			21	12	34						
262.0	266.3	09588	4.3	4.3	2C	2.60		1.29	3.40	25.00			5	9	15						
266.3	269.3	09589	3.0	3.0	2C	2.90	32	.44	1.50	12.00			2	37	39						
269.3	273.8	09590	4.5	4.5	2D	3.30		4.37	8.94	81.00			6	7	13						
273.8	278.4	09591	4.6	4.6	2D	3.20		2.31	3.95	44.00			5	7	13						
278.4	281.0	09592	2.6	2.6	1D12	2.90		.88	.86	20.00			3	3	6						
281.0	286.4	09593	5.4	5.4	2B	3.10	32	1.02	1.20	20.00			6	3	9						
286.4	291.7	09594	5.3	5.3	2H4	4.60		8.48	8.89	128.00			24	6	31						
291.7	297.5	09595	5.8	5.8	2F47	4.50		7.64	6.18	131.00			7	18	26						
297.5	301.0	09596	3.5	3.5	2H4	4.50		7.38	6.30	117.00			27	6	34						
301.0	304.2	09597	3.2	3.2	2H4	3.20	70	7.86	6.50	123.00			22	9	31						
304.2	308.0	09598	3.8	3.8	2E4	4.20		5.70	5.05	87.00			15	20	36						
308.0	311.0	09599	3.0	3.0	2E4	4.30		8.75	9.09	123.00			15	15	31						
311.0	315.0	09600	4.0	4.0	2D4	3.00	70	3.09	4.58	43.00			4	4	8						
315.0	321.0	09601	6.0	6.0	2D4	4.60		3.37	8.95	46.00			6	9	15						
321.0	325.5	09602	4.5	4.5	2H4	2.60		9.03	11.20	119.00			16	16	32						
325.5	331.0	09603	5.5	5.5	2H4	4.40	70	2.69	2.28	42.00			20	23	43						
331.0	336.0	09604	5.0	5.0	2H4	4.40		4.53	6.52	61.00			28	14	42						
336.0	341.5	09605	5.5	5.5	2H4	4.70		2.92	4.33	42.00			19	25	44						
341.5	343.5	09606	2.0	2.0	2D4	3.40		5.08	7.71	65.00			9	10	19						
343.5	345.5	09607	2.0	2.0	2E47	2.60		5.94	7.16	81.00			14	23	37						
345.5	349.5	09608	4.0	3.3	2E8	4.70		1.40	1.45	18.00			6	37	44						
349.5	353.1	09609	3.6	2.5	2E0	4.70	50	2.98	2.54	26.00			1	41	43						
353.1	358.0	09610	4.9	2.5	2E0	3.40		1.86	2.46	22.00			1	42	44						
358.0	361.0	09611	3.0	3.0	2E08	4.70		2.28	1.72	20.00			2	41	44						
361.0	365.4	09612	4.4	4.4	2E08	4.70		6.14	10.20	51.00			1	34	36						
365.4	370.9	09613	5.5	5.5	2E08	4.70		3.95	5.00	38.00			1	37	39						
372.5	376.0	09614	3.5	3.5	2E4	2.60		3.61	4.41	32.00			2	38	40						
376.0	380.0	09615	4.0	4.0	2E4	4.70	50	2.58	2.72	23.00			2	40	43						
380.0	383.2	09616	3.2	3.2	2E4	4.70		4.07	6.10	43.00			5	34	40						
383.2	387.5	09617	4.3	4.3	2E4	4.70		3.31	4.74	33.00			5	36	42						
387.5	392.0	09618	4.5	4.5	2H4	4.40		2.98	2.62	43.00			19	25	45						
392.0	395.0	09619	3.0	3.0	2E4	2.60	70	2.67	3.71	39.00			3	38	42						
395.0	396.7	09620	1.7	1.7	2E3	4.20		3.46	5.76	51.00			14	23	37						
396.7	421.9	09621	3.4	3.4	2H4	4.40	50	3.98	6.38	55.00			21	19	41						
421.9	425.2	09622	3.3	3.3	2C	2.60		1.17	3.70	97.00			6	6	12						
425.2	428.4	09623	3.2	3.2	2C	2.60		.61	1.58	15.00			5	6	11						
428.4	433.7	09624	5.3	5.3	2A	2.70	21	.93	2.23	14.00			1	1	3						
433.7	439.0	09625	5.3	5.3	2A	2.60		1.50	2.34	22.00			1	1	2						
439.0	444.2	09626	5.2	5.2	2A	2.90	21	1.81	1.21	14.00			2	3	6						
444.2	450.2	09627	6.0	6.0	2B	2.80		.82	.83	22.00			2	2	4						

199.9'
 4.12, 4.88, 5.706
 4.05, 4.71, 58.12

include Waste
 IDE?

DDH: 87F-06

-----DEPTHS-----						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %	S.G. W.R.	
181.0	185.4	09628	4.4	4.4	2B	2.80		.18	.06					3	5	8					
185.4	191.8	09629	6.4	6.4	2D47	3.40	33	3.77	12.40	26.00				11	5	16					
191.8	195.7	09630	3.9	3.9	2D4	3.10		2.57	6.69	24.00				3	7	11					
195.7	200.4	09631	4.7	4.7	2D4	3.20	33	1.05	7.73	14.00				3	11	14					
200.4	204.7	09632	4.3	4.3	2D4	4.70		3.07	7.74	32.00				2	11	13					
204.7	208.4	09633	3.7	3.7	2F4	3.20	50	5.60	7.09	69.00				5	31	37					
208.4	211.5	09634	3.1	3.1	2F4	4.50		6.70	7.34	91.00				7	29	36					
211.5	216.3	09635	4.8	4.8	2H4	4.30		5.62	6.93	87.00				29	10	40					
216.3	220.3	09636	4.0	4.0	2H4	4.30	70	5.27	7.37	79.00				28	12	40					
220.3	224.3	09637	4.0	4.0	2H4	4.30		3.89	6.51	60.00				23	18	41					
224.3	229.4	09638	5.1	5.1	2B	3.20		2.05	6.41	34.00				5	6	12					
229.4	233.6	09639	4.2	4.2	2B	3.00		1.82	3.97	28.00				3	4	7					
233.6	239.4	09640	5.8	5.8	2B	2.90	32	1.61	3.57	28.00				3	4	7					
239.4	244.6	09641	5.2	5.2	2B	3.20		2.23	6.43	63.00				10	3	14					
244.6	248.4	09642	3.8	3.8	2H4	3.90		3.52	14.00	87.00				24	7	31					
248.4	251.6	09643	3.2	3.2	2H4	4.50		6.46	12.00	120.00				32	7	40					
251.6	256.0	09644	4.4	4.4	2E4	3.30	50	4.21	6.27	50.00				3	35	38					
256.0	260.0	09645	4.0	4.0	2E4	4.70		2.74	5.90	27.00				1	40	41					
260.0	265.0	09646	5.0	5.0	2E4	2.70		4.70	6.63	43.00				6	35	41					
265.0	269.1	09647	4.1	4.1	2C	3.00		.59	3.89	12.00				3	7	10					
269.1	274.2	09648	5.1	4.6	2C	3.00	21	.26	2.59	12.00				4	7	11					
274.2	280.2	09649	6.0	5.5	2C	2.90		.65	2.55	25.00				3	4	7					
280.2	284.3	09650	4.1	4.1	2C	3.00		1.12	2.37	27.00				2	3	6					
284.3	289.5	09651	5.2	5.2	2A			1.05	3.06	19.00				1		2					
289.5	293.4	09652	3.9	3.9	2A		?	2.17	1.64	35.00				1	1	3					
293.4	298.9	09653	5.5	5.5	2A			1.49	3.66	21.00				1		1					
298.9	301.0	09654	2.1	2.1	2B	2.80		1.86	5.94	31.00				1		2					
301.0	304.5	09655	3.5	3.5	2B	3.90		2.01	2.68	10.00				1	1	3					
304.5	310.6	09656	6.1	6.1	2C	3.00	21	.46	.99	37.00				6	8	14					
310.6	314.7	09657	4.1	4.1	2A	3.00		.19	.89	14.00				6	8	14					
314.7	317.7	09658	3.0	3.0	2A	4.10		.32	.45	8.00				3	7	10					

7961
3.56, 7.44, 50.41

DDH: 87F-07

---DEPTHS---		SAMPLE INT. REC. ROCK S.G. S.G.	-----ASSAYS-----												S.G. W.R.						
FROM	TO		NO.	UNIT	PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe		BAO %	Hg %	Mn %	As %	Ba %	
246.0	250.4	09740	4.4	4.4	2C		1.50	.57	25.00				3	6	10						
250.4	253.7	09741	3.3	3.3	2C		1.28	1.47	25.00				4	10	14						
253.7	258.0	09742	4.3	4.3	2D4	33	8.85	16.10	62.00				3	9	12						
258.0	262.5	09743	4.5	4.5	2D4		7.37	13.90	44.00				2	36	39						
262.5	263.9	09744	1.4	1.4	2E4		2.97	4.36	33.00					32	33						
263.9	267.2	09745	3.3	3.3	2G	60	3.57	6.56	30.00					36	37						
267.2	270.0	09746	2.8	1.8	2E4		6.04	5.76	55.00				4	30	35						
270.0	272.1	09747	2.1	2.1	2G		3.28	5.49	36.00				1	35	36						
272.1	276.0	09748	3.9	3.9	1D09		.09	.10	4.00				3	4	7						
276.0	279.5	09749	3.5	3.5	1D09		.03	.06	6.00				3	2	6						
279.5	284.4	09750	4.9	4.9	1D09	Waste	.05	.08	4.00				3	4	7						
284.4	288.3	09751	3.9	3.9	1F49		.14	.08	4.00				3	3	7						
288.3	290.8	09752	2.5	2.5	1D29		.76	.85	14.00				2	3	6						
290.8	294.5	09753	3.7	3.7	1D19		3.12	1.90	9.00				2	2	5						
294.5	297.7	09754	3.2	3.2	1D19		1.06	1.60	26.00				5	6	11						
297.7	300.2	09755	2.5	2.5	2E4		4.70	6.49	39.00				5	22	28						
300.2	304.2	09756	4.0	4.0	2E4	50	4.09	8.05	25.00				3	26	29						
304.2	307.0	09757	2.8	2.8	2E4		3.13	5.61	23.00				6	28	35						
307.0	312.0	09758	5.0	5.0	2E		2.18	4.36	14.00				5	31	37						
312.0	316.3	09759	4.3	4.3	2E	50	3.15	5.52	21.00				1	34	36						
316.3	321.0	09760	4.7	4.7	2E		3.84	8.73	30.00				1	30	32						
321.0	325.0	09761	4.0	4.0	2E		2.24	6.05	21.00				1	35	37						
325.0	329.7	09762	4.7	4.7	2A		1.17	3.87	21.00				1	7	9						
329.7	335.0	09763	5.3	5.3	2C	21	2.43	4.55	31.00				4	5	10						
335.0	339.6	09764	4.6	4.6	2C		1.74	4.81	29.00				4	5	9						
339.6	343.6	09765	4.0	4.0	2A		2.19	4.45	35.00				1		2						
343.6	349.0	09766	5.4	5.4	2A	21	2.27	5.81	33.00				1		2						
349.0	352.8	09767	3.8	2.8	2A		.20	.57	21.00				4	8	13						
352.8	357.3	09768	4.5	4.5	2A		.75	1.26	17.00				2	2	5						

DDH: 87F-08

-----DEPTHS-----				-----ASSAYS-----																	
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %	S.G. W.R.	
102.2	105.7	09769	3.5	3.5	2C		.04	.10	6.00					12	13	25					
202.0	204.8	09770	2.8	2.8	2C		.12	.20	8.00					3	17	21					
204.8	205.7	09771	.9	.9	2D4		5.18	16.90	76.00					3	13	16					
205.7	207.5	09772	1.8	1.8	2E0	33	.15	2.39	6.00					1	40	42					
207.5	212.0	09773	4.5	4.5	2E14		4.30	7.47	59.00					10	25	35					
212.0	217.0	09774	5.0	5.0	2G4		7.67	6.94	106.00					5	14	20					
217.0	222.0	09775	5.0	5.0	2G4	60	7.88	7.61	116.00					4	16	20					
222.0	225.2	09776	3.2	3.2	2G4		9.83	8.50	145.00					3	11	15					
225.2	229.2	09777	4.0	4.0	2G4		3.88	5.47	57.00					2	22	25					
229.2	233.4	09778	4.2	4.2	1D19		.81	.96	12.00					4	4	8					
233.4	238.3	09779	4.9	4.9	1D19		.71	.16	14.00					5	2	8					
238.3	239.9	09780	1.6	1.6	2D	Waste	1.91	1.28	36.00					4	7	12					
239.9	244.0	09781	4.1	4.1	1D19	100	.06	.11	2.00					5	3	8					
244.0	249.2	09782	5.2	5.2	1D19		.06	.05	4.00					3	3	7					
249.2	252.8	09783	3.6	3.6	1D49		.56	.42	12.00					1	6	7					
252.8	256.6	09784	3.8	3.8	1D49		1.23	1.13	24.00					5	8	14					
256.6	262.0	09785	5.4	5.4	2A		.11	.15	2.00					2	2	5					
262.0	267.6	09786	5.6	5.6	2A		.77	.83	12.00					3	5	9					
267.6	272.0	09787	4.4	4.4	1D1		1.61	1.28	24.00					3	5	9					
272.0	275.7	09788	3.7	3.7	1D1		.07	.13	2.00					2	2	4					
275.7	278.4	09789	2.7	2.7	2C5		.37	.45	8.00					1	2	4					
278.4	282.0	09790	3.6	3.6	2L42		2.75	2.83	54.00					3	3	7					
282.0	286.4	09791	4.4	4.4	2L42		.40	.46	4.00					2	3	6					
286.4	289.2	09792	2.8	2.8	2E0		.33	.13	10.00					14	24	38					
289.2	292.0	09793	2.8	2.8	2D		4.74	6.19	71.00					6	7	13					
292.0	296.2	09794	4.2	4.2	2D	32	2.84	3.24	46.00					3	5	9					
296.2	297.8	09795	1.6	1.6	2A		.27	.35	4.00					2	2	4					
297.8	300.4	09796	2.6	2.6	1D49		.81	1.28	14.00					3	4	7					
300.4	303.3	09797	2.9	2.9	2E1		1.79	3.74	31.00					11	15	27					
303.3	306.1	09798	2.8	2.8	2E1		1.91	3.35	25.00					15	23	39					
306.1	309.0	09799	2.9	2.9	2H4	70	2.83	3.74	43.00					32	11	44					
309.0	313.1	09800	4.1	4.1	2H		1.68	1.66	22.00					18	23	41					
313.1	318.2	09801	5.1	5.1	2E0		4.21	8.43	38.00					3	32	36					
318.2	322.8	09802	4.6	4.6	2E0	50	2.48	4.24	23.00					2	37	40					
322.8	327.9	09803	5.1	5.1	2H4		3.21	5.51	37.00					30	13	43					
327.9	332.0	09804	4.1	4.1	2E4		2.67	4.87	21.00					2	36	39					
332.0	335.8	09805	3.8	3.8	2D		2.20	4.98	31.00					8	14	22					
335.8	339.0	09806	3.2	3.2	2D		2.06	3.27	39.00					7	12	20					
339.0	342.8	09807	3.8	3.8	10Q9	21	4.00	5.17	75.00					7	9	17					
342.8	347.0	09808	4.2	4.2	2D		1.63	6.07	33.00					4	5	9					
347.0	352.0	09809	5.0	5.0	2D		1.69	4.03	41.00					4	6	10					
352.0	356.5	09810	4.5	4.5	2D		2.08	3.98	48.00					6	10	16					
356.5	360.0	09811	3.5	3.5	2D		1.52	4.51	35.00					3	6	9					
360.0	363.8	09812	3.8	3.8	2D	21	2.77	3.17	66.00					7	6	14					
363.8	368.2	09813	4.4	4.4	2D		.95	2.41	2.00					5	3	9					
368.2	373.0	09814	4.8	4.8	2A		1.34	2.61	31.00					4	7	12					
373.0	377.0	09815	4.0	4.0	2A	21	1.71	4.35	29.00					2	2	4					
377.0	381.0	09816	4.0	4.0	2A		2.07	4.29	48.00					2	2	4					
381.0	386.0	09817	5.0	5.0	2A		1.71	3.42	2.00					1	1	3					
386.0	391.0	09818	5.0	5.0	2A	21	1.74	2.00	28.00					2	2	4					
391.0	396.0	09819	5.0	2.2	2A		.31	.44	14.00					7	7	14					

DDH: 87F-09

-----DEPTHS-----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %	S.G. W.R.	
278.8	286.0	09820	7.2	6.2	1F49		1.31	1.94	46.00					6	6	12					
286.0	291.7	09821	5.7	5.7	1F49	Waste	.38	.51	12.00					5	6	11					
291.7	301.0	09822	9.3	5.8	1D4		.10	.72	4.00					7	1	9					
301.0	305.0	09823	4.0	3.5	2E1		3.00	3.86	39.00					2	25	28					
305.0	310.0	09824	5.0	5.0	2E1	50	4.06	6.31	39.00					3	27	30					
310.0	315.0	09825	5.0	5.0	2E1		4.29	6.45	31.00					1	29	30					
315.0	320.0	09826	5.0	5.0	2E1		2.54	3.76	19.00						27	28					
320.0	325.0	09827	5.0	5.0	2E1		3.97	5.36	30.00						30	30					
325.0	330.5	09828	5.5	5.5	2E1	50	4.04	5.93	26.00						32	33					
330.5	334.4	09829	3.9	3.9	2D4		4.52	9.66	51.00					5	11	17					
334.4	338.0	09830	3.6	3.6	2E1		.66	3.12	12.00					1	28	30					
338.0	342.0	09831	4.0	4.0	2E1	40	.26	1.23	8.00					2	27	30					
342.0	347.0	09832	5.0	5.0	2E1		.88	1.82	10.00					2	28	30					
347.0	352.0	09833	5.0	5.0	2E1		.75	1.12	10.00					3	26	30					
352.0	357.0	09834	5.0	5.0	2E1		2.23	2.24	10.00					2	30	32					
357.0	359.0	09835	2.0	2.0	2E1		.02	.03	4.00					2		2					
359.0	362.1	09836	3.1	3.1	2E1	40	1.46	1.74	12.00					7	32	39					
362.1	365.0	09837	2.9	2.9	2F48		5.37	7.78	40.00					9	24	34					
365.0	368.5	09838	3.5	3.0	2E1		.80	1.81	8.00					4	24	28					
368.5	372.0	09839	3.5	3.5	2E1		2.85	5.01	20.00					2	13	15					
372.0	377.0	09840	5.0	5.0	2E1	40	.14	1.35	4.00					3	25	29					
377.0	382.0	09841	5.0	5.0	2E1		.20	1.18	6.00					3	29	32					
382.0	387.0	09842	5.0	5.0	2E1	40	.46	1.91	6.00					4	31	35					
387.0	392.0	09843	5.0	5.0	2E1	40	1.26	3.89	8.00					3	30	33					
392.0	396.0	09844	4.0	4.0	2E1		4.06	9.41	10.00					2	24	26					
396.0	400.8	09845	4.8	4.8	2D4		5.42	13.20	28.00					7	12	20					
400.8	407.6	09846	6.8	6.8	2C0	21	.82	1.09	10.00					3	5	8					
407.6	410.5	09847	2.9	2.9	2B4		6.30	14.30	55.00					5	6	12					

33.4
3.78, 5.84, 32.72

23.5
3.08, 7.21, 18.80

↑
missing
SG.
↓

↑
missing
Av.
↓

DDH: 87F-10

---DEPTHS---				-----ASSAYS-----																	
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %	S.G. W.R.	
162.7	168.0	09685	5.3	3.8	2C		.79	.90	15.00				4	19	24						
168.0	172.0	09686	4.0	4.0	2C		.08	.31	6.00				1	24	25						
172.0	175.2	09687	3.2	3.2	2C	33	.13	.46	8.00				3	23	26						
175.2	178.0	09688	2.8	2.8	2D4		2.68	8.29	28.00				2	11	14						
178.0	181.2	09689	3.2	3.2	2D4		3.81	9.24	33.00				2	11	14						
181.2	183.0	09690	1.8	1.8	2F4		6.54	11.50	43.00				2	30	33						
183.0	184.0	09691	1.0	1.0	2E4	50	1.24	3.02	12.00				1	32	34						
184.0	186.8	09692	2.8	2.8	2C		.68	4.05	8.00				1	15	16						
186.8	190.3	09693	3.5	3.5	2E46		3.94	8.46	27.00				1	34	36						
190.3	197.0	09694	6.7	6.7	1F49		.72	2.25	19.00				4	5	10						
197.0	200.8	09695	3.8	3.2	2E14		2.75	3.21	54.00				9	19	29						
200.8	211.4	09696	10.6	9.9	2AC	waste	.18	.28	4.00				2	1	4						
211.4	220.7	09697	9.3	8.8	1D149		.46	.41	8.00				2	4	7						
220.7	222.5	09698	1.8	1.8	1F49		.92	.48	20.00				4	5	10						
222.5	232.7	09699	10.2	9.9	2AC		.28	.43	4.00				1	1	3						
232.7	235.7	09700	3.0	3.0	1D49		2.76	1.92	50.00				5	34	40						
235.7	238.9	09701	3.2	3.2	2G42		6.31	9.36	78.00				9	30	40						
238.9	242.0	09702	3.1	2.6	2E14		8.21	9.67	99.00				9	26	36						
242.0	245.4	09703	3.4	3.4	2E14		9.33	13.80	113.00				14	15	29						
245.4	248.0	09704	2.6	2.6	2F444	50	11.90	22.60	140.00				4	19	24						
248.0	250.5	09705	2.5	2.5	2E14		4.99	7.74	72.00				10	5	15						
250.5	254.1	09706	3.6	3.6	10Q9		6.18	1.06	157.00				4	16	21						
254.1	263.5	09707	9.4	3.1	2E4		6.58	10.40	54.00				8	26	35						
263.5	265.5	09708	2.0	2.0	2E1	50	1.72	4.03	22.00				5	29	34						
265.5	270.7	09709	5.2	5.2	2F4		3.56	5.57	42.00				4	34	38						
270.7	274.6	09710	3.9	3.4	2F4		4.06	7.29	38.00				2	35	37						
274.6	278.0	09711	3.4	2.9	2E18		2.65	3.34	21.00				4		4						
278.0	282.0	09712	4.0	4.0	2E18		2.62	3.18	30.00				5	27	33						
282.0	285.5	09713	3.5	3.5	2E18	50	2.75	2.80	37.00				8	5	13						
285.5	289.5	09714	4.0	4.0	2E481		4.53	5.30	56.00				6	32	39						
289.5	293.9	09715	4.4	4.4	2E18		4.88	5.08	47.00				3	15	19						
293.9	297.0	09716	3.1	3.1	2E18		3.67	5.17	30.00				4	29	34						
297.0	301.7	09717	4.7	4.2	2E18	50	3.93	5.55	19.00				5	17	22						
301.7	304.3	09718	2.6	2.6	2E18		5.37	7.85	21.00				3	29	32						
304.3	312.0	09719	7.7	3.2	2F4		3.64	7.26	14.00				3	30	34						
312.0	317.0	09720	5.0	3.8	2F4		3.73	6.02	16.00				1	38	39						
317.0	319.5	09721	2.5	2.5	2F4	50	2.64	8.36	17.00				1	32	33						
319.5	324.2	09722	4.7	4.7	2E4		5.04	12.80	30.00				1	21	23						
324.2	328.5	09723	4.3	4.3	2E4		3.76	9.81	20.00				1	29	30						
328.5	332.0	09724	3.5	3.5	2E4		2.22	4.83	14.00				1	12	14						
332.0	336.9	09725	4.9	4.9	2E0	50	2.06	3.56	12.00				1	38	39						
336.9	341.5	09726	4.6	4.6	2E0		2.87	5.32	16.00				1	14	16						
341.5	344.4	09727	2.9	2.9	2B45		4.51	5.59	16.00				2	2	4						
344.4	348.7	09728	4.3	4.3	2A4		1.13	2.51	21.00				1	1	2						
348.7	353.2	09729	4.5	4.5	2D45	21	2.33	4.87	17.00				5	9	14						
353.2	357.0	09730	3.8	2.8	2D45		2.36	.85	49.00				1	31	33						
357.0	360.0	09731	3.0	2.3	2D45		5.64	12.50	28.00				2	16	19						
360.0	363.7	09732	3.7	.7	2A		3.29	7.89	14.00				1	32	34						
363.7	368.2	09733	4.5	4.5	2A		1.75	5.18	23.00				1	13	15						
368.2	371.3	09734	3.1	3.1	2A	21	2.24	9.40	17.00				3	11	14						
371.3	375.0	09735	3.7	3.7	2A		1.74	4.01	16.00				2	5	8						

DDH: 87F-10

-----DEPTHS-----				-----ASSAYS-----																	
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %	S.G. W.R.	
375.0	380.0	09736	5.0	5.0	2A		.73	3.50	10.00			5	9	15							
380.0	385.0	09737	5.0	5.0	2A		.37	.91	19.00			2	8	10							
385.0	390.6	09738	5.6	5.6	2A	21	.85	3.09	18.00			1	32	34							
390.6	395.5	09739	4.9	4.9	2A		1.47	4.17	26.00			2	27	30							

DDH: 87F-11

---DEPTHS---		SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														S.G. W.R.
FROM	TO					CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %	
59.9	63.6	09851	3.7	3.7	2G234			10.10	17.90	200.00				16	10	26				
63.6	67.5	09852	3.9	3.9	2G234	60		8.26	14.70	148.00				12	14	27				
67.5	72.9	09853	5.4	5.4	2G234			10.20	14.50	152.00				25	4	30				
72.9	77.8	09854	4.9	4.9	2G234			8.14	13.50	95.00				14	14	28				
77.8	83.0	09855	5.2	5.2	2G234	60		4.54	7.77	46.00				1	27	29				
83.0	88.2	09856	5.2	5.2	2G234			4.61	8.24	42.00				1	15	17				
88.2	96.0	09857	7.8	1.6	2E4			6.27	14.70	54.00				1	30	32				
96.0	99.0	09858	3.0	3.0	2E1			1.42	4.57	18.00					27	28				
99.0	102.0	09859	3.0	3.0	2E1	50		3.09	5.76	36.00				1	16	18				
102.0	106.6	09860	4.6	4.6	2E1			2.60	2.85	38.00				5	30	36				
106.6	111.4	09861	4.8	4.8	1D29			.24	.36	8.00				2	8	11				
111.4	118.0	09862	6.6	6.6	1D29			.06	.11	.10				2	1	4				
118.0	126.2	09863	8.2	8.2	1D489	waste		.14	.08	2.00				2	2	5				
126.2	133.5	09864	7.3	7.3	1D219			.26	.30	4.00				1	2	4				
133.5	139.9	09865	6.4	6.4	1D219			1.91	2.74	34.00				4	5	9				
139.9	146.2	09866	6.3	6.3	1D219			2.43	1.69	40.00				2	26	28				
146.2	148.5	09867	2.3	2.3	2D4			6.44	5.16	105.00				6	9	16				
148.5	152.0	09868	3.5	3.5	2E1			5.52	9.54	73.00				10	24	34				
152.0	157.0	09869	5.0	4.5	2E1	50		4.93	6.94	67.00				10	25	35				
157.0	162.1	09870	5.1	5.1	2E1			1.96	2.73	30.00				8	32	40				
162.1	167.3	09871	5.2	4.2	2E1			1.46	1.46	20.00				4	30	35				
167.3	172.0	09872	4.7	4.7	2D0			1.04	3.52	20.00				3		3				
172.0	175.5	09873	3.5	3.5	2D0	32		1.03	4.37	16.00				3	3	6				
175.5	180.0	09874	4.5	4.5	2D0			.67	.65	12.00				4	7	11				
180.0	185.0	09875	5.0	5.0	2E1			1.66	3.40	22.00				6	26	33				
185.0	190.0	09876	5.0	3.0	2E1	50		3.63	3.85	42.00				6	27	34				
190.0	195.0	09877	5.0	5.0	2E1			1.90	2.99	24.00				4	29	33				
195.0	200.0	09878	5.0	5.0	2E1			2.03	3.21	24.00				6	32	38				
200.0	205.0	09879	5.0	5.0	2E1			2.85	5.34	25.00				1	31	32				
205.0	211.0	09880	6.0	6.0	2E1	50		2.91	5.19	30.00				6	30	37				
211.0	215.7	09881	4.7	4.7	2E1			2.36	4.30	16.00				3	33	36				
215.7	220.0	09882	4.3	4.3	2D			2.82	4.58	27.00				4	5	9				
220.0	223.9	09883	3.9	3.9	2D	32		2.77	7.27	39.00				2	3	5				
223.9	228.1	09884	4.2	4.2	2D			2.69	4.17	37.00				2	3	6				
228.1	233.9	09885	5.8	5.8	2D			3.03	7.36	31.00				4	7	12				
233.9	237.0	09886	3.1	3.1	2H4	32		5.21	13.10	37.00				13	21	35				
237.0	242.3	09887	5.3	4.3	2D0			3.51	7.86	30.00				7	6	13				
242.3	246.5	09888	4.2	4.2	2E4			5.01	14.40	40.00				2	26	29				
246.5	252.0	09889	5.5	5.5	2E4	50		6.50	15.00	41.00				3	24	27				
252.0	254.4	09890	2.4	2.4	2E4			4.93	10.30	25.00				4	30	35				
254.4	257.5	09891	3.1	3.1	2A4			3.32	7.85	23.00				9	29	38				
257.5	260.1	09892	2.6	2.6	2A4			2.94	6.05	21.00				2	6	9				
260.1	264.8	09893	4.7	4.7	2D4	21		1.86	18.60	21.00				5	8	13				
264.8	267.0	09894	2.2	.2	2D			2.11	5.73	24.00				5	8	14				
267.0	272.0	09895	5.0	5.0	2D			.94	4.30	14.00				5	6	11				
272.0	277.0	09896	5.0	5.0	2D			1.95	5.10	28.00				4	4	9				
277.0	282.0	09897	5.0	5.0	2D			1.96	4.35	26.00				4	14	18				
282.0	285.4	09898	3.4	3.4	2D	21		.66	3.46	14.00					13	14				
285.4	289.5	09899	4.1	3.3	2A			.85	2.76	18.00				4	4	8				
289.5	293.3	09900	3.8	3.8	2A			.28	1.30	6.00				3	19	22				

DDH: 87F-12

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													
FROM	TO						CU %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BAO %	Hg %	Mn %	As %	Ba %
169.2	170.5	09659	1.3	1.3	2D4		4.91	10.60	76.00				5	7	13					
170.5	174.4	09660	3.9	3.9	2E164	60	10.40	12.10	140.00				11	17	29					
174.4	180.1	09661	5.7	5.7	2H4		5.73	7.62	96.00				23	15	38					
180.1	183.9	09662	3.8	3.8	2G4		4.04	6.23	73.00				3	17	20					
183.9	187.0	09663	3.1	3.1	1H49		.96	1.02	18.00				4	5	10					
187.0	192.0	09664	5.0	5.0	1D49		.44	.64	10.00				3	3	6					
192.0	195.1	09665	3.1	3.1	2AC	Waste	.03	.08	2.00				1	1	3					
195.1	199.0	09666	3.9	3.9	2AC		1.16	1.11	28.00				3	5	9					
199.0	203.1	09667	4.1	4.1	1F49		.48	.40	2.00					5	6					
203.1	206.1	09668	3.0	3.0	2AC		.57	.55	10.00				3	4	8					
206.1	209.3	09669	3.2	3.2	2E1		1.58	3.71	12.00				7	15	23					
209.3	212.4	09670	3.1	3.1	2E1		2.25	1.33	3.00					30	31					
212.4	215.8	09671	3.4	3.4	2E1	50	.42	1.68	8.00				7	14	21					
215.8	219.8	09672	4.0	4.0	2H4		3.40	6.85	48.00				18	17	36					
219.8	223.0	09673	3.2	3.2	2E1		2.07	4.63	35.00				9	17	27					
223.0	228.5	09674	5.5	3.5	2F4	50	4.21	8.83	37.00				3	34	38					
228.5	233.1	09675	4.6	4.6	2F4		4.24	12.10	35.00				7	27	35					
233.1	237.6	09676	4.5	4.5	2F4		2.78	6.26	26.00				11	20	31					
237.6	242.5	09677	4.9	4.9	2D	3.24	2.82	7.44	39.00				7	7	14					
242.5	246.0	09678	3.5	3.5	2D	2.86	3.44	5.45	58.00				4	3	8					
246.0	249.1	09679	3.1	3.1	2D	3.42 3.2	2.38	8.97	39.00				5	6	11					
249.1	252.6	09680	3.5	3.5	2D	3.31	5.05	4.64	81.00				7	9	17					
252.6	257.2	09681	4.6	4.6	2E1	3.61	1.11	2.44	32.00				12	17	29					
257.2	261.5	09682	4.3	4.3	2E1	3.40	1.12	3.56	28.00				9	14	23					
261.5	266.0	09683	4.5	4.5	2E1	3.50	4.07	7.98	101.00				10	11	22					
266.0	271.1	09684	5.1	5.1	2D	2.1	2.52	3.29	44.00				8	2	11					

**THIS REPORT WAS REQUESTED BY: LEEP GEOLOGY AT: 09:53:09

↑
Murray
←