

only a minor constituent overall. Carbon content is normally within the 1/4 to 1/2 % range and generally occurs in thin coatings concentrated on thin cleavage surfaces (S1 and S2 surfaces). Chalcopyrite occurs locally in traces as small blebs within sulphide bands and fractures.

Total sulphide content is variable from 15% to 30% and may locally range up to 60%.

4a rock types are more abundant than any other ore facies at Grum and constitute 53% of the millfeed in the I.V. stage 1 pit and 49% of the I.V. ultimate pit millfeed.

Composite G2: 4d Ore Type

Unit 4d is light to medium grey, moderately hard to locally very hard, usually well banded (at Grum) generally well foliated (at Grum), micaceous, pyritic quartzite. The unit is texturally and mineralogically similar to 4a at Grum except that carbon is less abundant. Banding is commonly less well developed and sulphide bands in the high grade ore are characteristically redder in colour and contain less pyrite than 4a. 4d feed grade is slightly higher and gold content is slightly elevated over 4a values. At Grum, contacts with 4a ore are commonly gradational over a few feet making a "clean" separation of these ore types at a mining scale difficult. Included in composite G2 are a few samples of moderately carbonaceous intervals occurring within thick intervals of non-carbonaceous quartzite ore to create a more representative millfeed sample.

4d rock types represent 14% of the millfeed from both the I.V. stage 1 pit and the I.V. ultimate pit.

Composite G3: 4e Ore Type

Dominant rock type of this composite is massive pyritic sulphide (4e) which may locally contain up to 10-30% barite (4g). At Grum, the 4e massive pyritic sulphide is the dominant massive sulphide species. The massive sulphides consist of banded to homogeneous, usually weakly foliated fine grained (at Grum) massive pyrite +/- barite with lesser sphalerite and galena. Total sulphide +/- sulphate content is at least 60%, generally greater than 80% and commonly near 100%. Gangue consists of quartz +/- barite +/- carbonates (calcite, dolomite, ankerite). Accessory minerals include pyrrhotite, magnetite, chalcopyrite, arsenopyrite, and marcasite.

This ore facies is the highest grade millfeed from Grum and represents 33 % of the feed from the I.V. Stage 1 pit and 37% of the I.V. ultimate millfeed.

This composite contains the least amount of sample from the 87 and 88 drilling programs. It is also much higher grade than predicted by the diluted Grum model and is probably the least representative of actual feed composition. It is recommended that a low priority be put on testing massive sulphide until additional sample is collected. 20 holes are planned to be drilled at Grum this summer and additional holes

targeted to intersect thick massive sulphide may be drilled if necessary.

Composite Statistics: Composite weight and assays are calculated from individual sample assays. (weighted to recovered interval * SG)

| Comp. | Ore Type | kilograms | SG | %Pb | %Zn | Ag g/t | Au g/t |
|-------|----------|-----------|------|------|-------|-----------|-----------|
| G1 | 4a | 524 | 3.03 | 2.90 | 5.44 | 48.48 | 0.72 |
| G2 | 4d | 217 | 3.07 | 3.80 | 6.38 | 63.71 | 0.82 |
| G3 | 4e | 191 | 3.78 | 4.91 | 10.09 | 87.28 | 0.93 |

Diluted G8705 Model Feed Predictions - I.V. Grum Stage 1 Pit
Model diluted 15% at 0 grade Cutoff = 5% Pb+Zn

| Comp. | Ore Type | Tonnes *1000 | %Feed | %Pb | %Zn | Ag g/t | Au g/t |
|-------|----------|-----------------|-------|------|------|-----------|-----------|
| G1 | 4a | 3,514 | 53% | 2.32 | 4.25 | 39.13 | 0.73 |
| G2 | 4d | 927 | 14% | 3.62 | 6.43 | 58.61 | 0.80 |
| G3 | 4e | 2,170 | 33% | 4.60 | 6.77 | 73.83 | 0.88 |
| Total | | 6,611 | 100% | 3.25 | 5.38 | 53.25 | 0.79 |

Diluted G8705 Model Feed Predictions - Ultimate I.V. Grum Pit
Model diluted 15% at 0 grade Cutoff = 5% Pb+Zn

| Comp. | Ore Type | Tonnes *1000 | %Feed | %Pb | %Zn | Ag g/t | Au g/t |
|-------|----------|-----------------|-------|------|------|-----------|-----------|
| G1 | 4a | 10,516 | 49% | 2.37 | 4.23 | 40.12 | 0.75 |
| G2 | 4d | 2,974 | 14% | 3.18 | 5.70 | 52.67 | 0.77 |
| G3 | 4e | 7,777 | 37% | 4.39 | 6.95 | 73.36 | 1.01 |
| Total | | 21,267 | 100% | 3.22 | 5.43 | 54.03 | 0.84 |

Composite Number : COMP 63

Estimate of Composite Weight:

191 KILOGRAMS

Description:

Dominately massive pyritic +/- barite sulphide ore types - 4e and 4g - selected intervals contain nonporous samples and have total oxidation (or = 2

Total Intervals:

64

| SAMPLE DDID | FROM (ft) | TO (ft) | INT. (ft) | REC.# (ft) | ACT REC (ft) | REC. (%) | ROCK TYPE | PULP S.G. | Z Pb+2a | Z Pb | Z Zn | Ag (g/ton) | Au (g/ton) | ZSO4 Fe | ZINSOL Fe | ZTOTAL Fe | Weathering | Porous/ Nonporous | Core Oxidation | Split Oxidation | Total Oxidation |
|--|-----------|---------|-----------|------------|--------------|----------|-----------|-----------|---------|-------|-------|------------|------------|---------|-----------|-----------|------------|-------------------|----------------|-----------------|-----------------|
| TOTAL: | | | 259.6 | 280 | 244.5 | 94.2 | | | | | | | | | | | | | | | |
| SG & INTERVAL LENGTH WEIGHTED AVERAGE: | | | | | | | | 3.78 | 15.00 | 4.91 | 10.09 | 87.28 | 0.93 | 3.40 | 18.44 | 21.84 | | | | | |
| 30426 876-03 | 194.8 | 197.0 | 2.2 | 2.6 | 2.2 | 100 | 464 | 3.4 | 17.63 | 5.73 | 11.90 | 95.0 | 0.82 | 3.44 | 9.86 | 13.30 | 0 np | | 0 | 0 | 0 |
| 30427 876-03 | 197.0 | 203.0 | 6.0 | 7.7 | 6.0 | 100 | 5A196 | 2.7 | 1.51 | 0.50 | 1.01 | 11.0 | 0.55 | 1.78 | 5.73 | 7.51 | 0 np | | 0 | 0 | 0 |
| 30428 876-03 | 203.0 | 208.0 | 5.0 | 6.1 | 5.0 | 100 | 4E4 | 4.1 | 22.54 | 8.54 | 14.00 | 148.0 | 1.58 | 1.67 | 22.93 | 24.60 | 0 np | | 0 | 0 | 0 |
| 30429 876-03 | 208.0 | 213.1 | 5.1 | 5.6 | 5.1 | 100 | 4E4 | 4 | 16.01 | 5.91 | 10.10 | 91.0 | 1.92 | 2.35 | 27.95 | 30.30 | 0 np | | 0 | 0 | 0 |
| 30430 876-03 | 214.6 | 217.4 | 2.8 | 3.9 | 2.8 | 100 | 464 | 4 | 12.00 | 3.50 | 8.50 | 59.0 | 1.10 | 0.53 | 8.07 | 8.60 | 0 np | | 0 | 0 | 0 |
| 30431 876-03 | 217.4 | 220.8 | 3.4 | 3.1 | 3.1 | 91 | 4E44 | 4.4 | 28.80 | 11.00 | 17.80 | 153.0 | 1.44 | 7.46 | 17.74 | 25.20 | 0 np | | 0 | 0 | 0 |
| 30432 876-03 | 220.8 | 225.0 | 4.2 | 5.0 | 4.2 | 100 | 464 | 4.4 | 14.95 | 5.49 | 9.46 | 109.0 | 0.89 | 0.74 | 14.66 | 15.40 | 0 np | | 0 | 0 | 0 |
| 30433 876-03 | 225.0 | 229.0 | 4.0 | 4.8 | 4.0 | 100 | 464 | 4.5 | 12.04 | 3.99 | 8.05 | 97.0 | 0.96 | 0.47 | 16.33 | 16.80 | 0 np | | 0 | 0 | 0 |
| 30434 876-03 | 229.0 | 233.5 | 4.5 | 4.6 | 4.5 | 100 | 464 | 4.3 | 12.72 | 4.84 | 7.88 | 91.0 | 1.13 | 8.79 | 8.11 | 16.90 | 0 np | | 0 | 0 | 0 |
| 30435 876-03 | 233.5 | 238.1 | 4.6 | 5.0 | 4.6 | 100 | 464 | 4.5 | 9.96 | 3.75 | 6.21 | 72.0 | 0.96 | 0.40 | 19.90 | 20.30 | 0 np | | 0 | 0 | 0 |
| 30436 876-03 | 238.1 | 242.1 | 4.0 | 5.0 | 4.0 | 100 | 4E4 | 4.4 | 12.19 | 5.04 | 7.15 | 96.0 | 1.37 | 0.88 | 28.92 | 29.80 | 0 np | | 0 | 0 | 0 |
| 30437 876-03 | 242.1 | 246.5 | 4.4 | 5.0 | 4.4 | 100 | 4E4 | 4.5 | 11.53 | 4.78 | 6.75 | 113.0 | 1.30 | 0.64 | 31.46 | 32.10 | 0 np | | 0 | 0 | 0 |
| 30438 876-03 | 246.5 | 250.5 | 4.0 | 4.2 | 4.0 | 100 | 4E0 | 3.9 | 4.16 | 2.47 | 1.69 | 61.0 | 1.10 | 1.42 | 32.98 | 34.40 | 0 np | | 0 | 0 | 0 |
| 30439 876-03 | 250.5 | 254.8 | 4.3 | 4.9 | 4.3 | 100 | 360 | 2.8 | 0.18 | 0.06 | 0.12 | 4.0 | 0.14 | 2.04 | 2.34 | 4.38 | 0 np | | 0 | 0 | 0 |
| 30440 876-03 | 254.8 | 258.4 | 3.6 | 4.5 | 3.6 | 100 | 4E6 | 4.2 | 9.95 | 4.90 | 5.05 | 66.0 | 0.96 | 1.57 | 31.93 | 33.50 | 0 np | | 0 | 0 | 0 |
| 30441 876-03 | 258.4 | 262.0 | 3.6 | 4.3 | 3.6 | 100 | 4E8 | 4.5 | 14.49 | 5.53 | 8.96 | 82.0 | 0.89 | 0.65 | 21.35 | 22.00 | 0 np | | 0 | 0 | 0 |
| 30870 876-05 | 198.6 | 203.0 | 4.4 | 4.6 | 4.4 | 100 | 5D4 | 3 | 10.24 | 1.80 | 8.44 | 32.0 | 0.55 | 6.99 | 13.51 | 26.50 | 0 np | | 0 | 0 | 0 |
| 30871 876-05 | 203.0 | 207.0 | 4.0 | 4.8 | 4.0 | 100 | 5D4 | 4.3 | 24.75 | 6.75 | 18.00 | 129.0 | 1.23 | 6.86 | 17.74 | 24.60 | 0 np | | 0 | 0 | 0 |
| 30873 876-05 | 212.0 | 216.7 | 4.7 | 6.3 | 4.7 | 100 | 4E4 | 4.6 | 30.00 | 7.90 | 22.10 | 114.0 | 0.69 | 1.76 | 25.74 | 27.50 | 0 np | | 0 | 0 | 0 |
| 30874 876-05 | 216.7 | 221.4 | 4.7 | 4.8 | 4.7 | 100 | 4E4 | 4.4 | 36.96 | 9.86 | 27.10 | 137.0 | 0.89 | 1.60 | 19.80 | 21.40 | 0 np | | 0 | 0 | 0 |
| 30875 876-05 | 221.4 | 227.0 | 5.6 | 5.4 | 5.4 | 96 | 4E4 | 4.7 | 18.91 | 1.01 | 17.90 | 178.0 | 0.96 | 0.99 | 26.31 | 27.30 | 0 np | | 0 | 0 | 0 |
| 30876 876-05 | 227.0 | 232.0 | 5.0 | 1.9 | 1.9 | 38 | 4E4 | 4.6 | 9.10 | 2.68 | 6.42 | 31.0 | 0.48 | 1.38 | 39.12 | 40.50 | 0 np | | 0 | 0 | 0 |
| 30877 876-05 | 232.0 | 237.4 | 5.4 | 5.3 | 5.3 | 98 | 4E4 | 4.4 | 16.33 | 4.43 | 11.90 | 74.0 | 0.75 | 1.73 | 31.57 | 33.30 | 0 np | | 0 | 0 | 0 |
| 30878 876-05 | 237.4 | 242.6 | 5.2 | 4.8 | 4.8 | 92 | 4E4 | 4.5 | 24.18 | 6.98 | 17.20 | 99.0 | 1.03 | 4.44 | 25.86 | 30.30 | 0 np | | 0 | 0 | 0 |
| 30879 876-05 | 242.6 | 246.8 | 4.2 | 4.0 | 4.0 | 95 | 4E4 | 4 | 34.10 | 11.20 | 22.90 | 201.0 | 1.78 | 2.75 | 15.95 | 18.70 | 0 np | | 0 | 0 | 0 |
| 30880 876-05 | 246.8 | 249.6 | 2.8 | 4.9 | 2.8 | 100 | 4E4 | 4.5 | 14.06 | 4.18 | 9.88 | 75.0 | 1.27 | 3.56 | 31.74 | 35.30 | 0 np | | 0 | 0 | 0 |
| 30886 876-05 | 338.0 | 344.1 | 6.1 | 5.6 | 5.6 | 92 | 4E4 | 4 | 14.12 | 4.56 | 9.56 | 79.0 | 1.17 | 2.96 | 27.34 | 30.30 | 0 np | | 0 | 0 | 0 |
| 30887 876-05 | 344.1 | 348.0 | 3.9 | 4.1 | 3.9 | 100 | 5D4 | 3.3 | 7.52 | 1.55 | 5.97 | 21.0 | 0.62 | 8.96 | 12.74 | 21.70 | 0 np | | 0 | 0 | 0 |
| 30888 876-05 | 348.0 | 354.7 | 6.7 | 4.3 | 4.3 | 64 | 4E4 | 4.2 | 15.48 | 5.08 | 10.40 | 98.0 | 1.03 | 1.18 | 23.72 | 24.90 | 0 np | | 0 | 0 | 0 |
| 30889 876-05 | 354.7 | 358.3 | 3.6 | 3.7 | 3.6 | 100 | 4E4 | 4.2 | 12.80 | 3.99 | 8.81 | 75.0 | 0.62 | 2.48 | 30.22 | 32.70 | 0 np | | 0 | 0 | 0 |
| 30890 876-05 | 358.3 | 363.0 | 4.7 | 2.8 | 2.8 | 60 | 4L023 | 2.9 | 1.19 | 0.37 | 0.82 | 6.0 | 0.14 | 1.02 | 10.28 | 11.30 | 0 np | | 0 | 0 | 0 |
| 30891 876-05 | 363.0 | 367.0 | 4.0 | 5.0 | 4.0 | 100 | 4E4 | 3.9 | 15.91 | 5.51 | 10.40 | 97.0 | 1.30 | 3.32 | 21.48 | 24.80 | 0 np | | 0 | 0 | 0 |
| 30892 876-05 | 367.0 | 371.8 | 4.8 | 4.9 | 4.8 | 100 | 4E4 | 4.3 | 19.45 | 6.25 | 13.20 | 93.0 | 1.30 | 4.27 | 27.73 | 32.00 | 0 np | | 0 | 0 | 0 |
| 30893 876-05 | 371.8 | 374.0 | 2.2 | 2.4 | 2.2 | 100 | 4A34 | 3.5 | 9.64 | 3.42 | 6.22 | 54.0 | 1.65 | 3.42 | 17.88 | 21.30 | 0 np | | 0 | 0 | 0 |
| 30813 878-11 | 190.0 | 193.0 | 3.0 | 4.7 | 3.0 | 100 | 4E4 | 4.1 | 22.36 | 6.96 | 15.40 | 136.0 | 0.96 | 18.70 | 7.80 | 26.50 | 0 np | | 0 | 0 | 0 |
| 30814 878-11 | 193.0 | 196.3 | 3.3 | 3.3 | 3.3 | 100 | 4E4 | 4.4 | 25.87 | 8.77 | 17.10 | 180.0 | 1.58 | 1.35 | 26.65 | 28.00 | 0 np | | 0 | 0 | 0 |
| 30815 878-11 | 196.3 | 203.7 | 7.4 | 8.1 | 7.4 | 100 | 5C44 | 2.9 | 4.93 | 0.48 | 4.45 | 8.0 | 0.10 | 8.96 | 1.74 | 10.70 | 0 np | | 0 | 0 | 0 |
| 30942 876-12 | 307.0 | 309.5 | 2.5 | 2.6 | 2.5 | 100 | 5B62 | 2.9 | 1.87 | 0.79 | 1.08 | 11.0 | 0.07 | 2.66 | 2.78 | 5.44 | 0 np | | 0 | 0 | 0 |
| 30943 876-12 | 309.5 | 316.5 | 7.0 | 7.7 | 7.0 | 100 | 5B6 | 2.9 | 0.33 | 0.04 | 0.29 | 0.0 | 0.05 | 2.87 | 2.25 | 5.12 | 0 np | | 0 | 0 | 0 |
| 30944 878-12 | 316.5 | 320.4 | 3.9 | 4.6 | 3.9 | 100 | 4A4 | 2.6 | 6.72 | 1.96 | 4.76 | 34.0 | 0.27 | 0.97 | 0.79 | 1.76 | 0 np | | 0 | 0 | 0 |
| 30945 876-12 | 320.4 | 322.6 | 2.2 | 3.1 | 2.2 | 100 | 4E4 | 3.3 | 10.29 | 3.36 | 6.93 | 61.0 | 0.27 | 2.63 | 12.77 | 15.40 | 0 np | | 0 | 0 | 0 |
| 30946 876-12 | 322.6 | 325.5 | 2.9 | 3.2 | 2.9 | 100 | 4E4 | 3.6 | 14.15 | 5.05 | 9.10 | 96.0 | 0.41 | 1.37 | 17.73 | 19.10 | 0 np | | 0 | 0 | 0 |

| SAMPLE | DDHID | FROM | TO | INT. | REC.* | ACT | REC. | ROCK | PULP | Z | | | Ag | Au | ZSDL | ZINSOL | ZTOTAL | Weather- | Porous/ | Core | Split | Total |
|--------|--------|-------|-------|------|-------|-----|------|-------|------|-------|-------|-------|---------|---------|-------|--------|--------|----------|-----------|-----------|-----------|-----------|
| | | (ft) | (ft) | (ft) | (ft) | REC | (%) | TYPE | S.G. | Pb+Zn | Pb | Zn | (g/ton) | (g/ton) | Fe | Fe | Fe | ing | Nonporous | Oxidation | Oxidation | Oxidation |
| | | 277.3 | 280.8 | 3.5 | 4.1 | 3.5 | 100 | 4E4 | 3.2 | 13.43 | 5.11 | 8.32 | 101.0 | 0.69 | 2.93 | 11.07 | 14.00 | 0 | no | 0 | 0 | 0 |
| 30520 | 876-14 | 277.3 | 280.8 | 3.5 | 4.1 | 3.5 | 100 | 4E4 | 3.2 | 13.43 | 5.11 | 8.32 | 101.0 | 0.69 | 2.93 | 11.07 | 14.00 | 0 | no | 0 | 0 | 0 |
| 30521 | 876-14 | 280.8 | 284.2 | 3.4 | 3.7 | 3.4 | 100 | 4E4 | 3.9 | 24.37 | 8.67 | 15.70 | 155.0 | 1.30 | 4.85 | 13.35 | 18.20 | 0 | np | 0 | 0 | 0 |
| 30522 | 876-14 | 284.2 | 288.6 | 4.4 | 4.4 | 4.4 | 100 | 5D8 | 2.9 | 1.95 | 0.46 | 1.49 | 10.0 | 0.14 | 5.89 | 2.38 | 8.27 | 0 | np | 0 | 0 | 0 |
| 30523 | 876-14 | 288.6 | 292.8 | 4.2 | 4.7 | 4.2 | 100 | 5D8 | 2.8 | 0.44 | 0.26 | 0.18 | 4.0 | 0.07 | 5.95 | 0.34 | 6.29 | 0 | np | 0 | 0 | 0 |
| 30524 | 876-14 | 292.8 | 296.5 | 3.7 | 4.3 | 3.7 | 100 | 4A34 | 3.3 | 14.67 | 3.47 | 11.20 | 62.0 | 1.17 | 2.46 | 9.74 | 12.20 | 0 | np | 0 | 0 | 0 |
| 30455 | 876-14 | 239.8 | 242.0 | 2.2 | 2.0 | 2.0 | 91 | 4E468 | 3 | 23.72 | 7.92 | 15.80 | 113.0 | 1.37 | 3.54 | 19.66 | 23.20 | 0 | np | 0 | 0 | 0 |
| 16971 | 886-01 | 157.0 | 162.5 | 5.5 | 6.7 | 5.5 | 100 | 4A4 | 3 | 13.83 | 4.55 | 9.28 | 72.0 | 0.34 | 2.81 | 1.84 | 4.65 | 1 | np | 0 | 0 | 1 |
| 16972 | 886-01 | 162.5 | 166.8 | 4.3 | 4.8 | 4.3 | 100 | 4D0 | 2.9 | 5.66 | 1.37 | 4.29 | 24.0 | 0.07 | 6.34 | 4.06 | 10.40 | 0 | np | 0 | 0 | 0 |
| 16973 | 886-01 | 166.8 | 171.6 | 4.8 | 1.3 | 1.3 | 27 | 5C4 | 2.5 | 3.21 | 0.20 | 3.01 | 5.0 | 0.14 | 13.20 | 4.20 | 17.40 | 0 | np | 0 | 0 | 0 |
| 16974 | 886-01 | 171.6 | 172.7 | 1.1 | 1.0 | 1.0 | 91 | 4E0 | 3.8 | 3.19 | 0.87 | 2.32 | 5.0 | 1.03 | 0.90 | 35.10 | 36.00 | 0 | no | 0 | 0 | 0 |
| 16975 | 886-01 | 172.7 | 177.4 | 4.7 | 4.8 | 4.7 | 100 | 4D0 | 2.8 | 3.99 | 1.11 | 2.88 | 17.0 | 0.75 | 1.16 | 7.54 | 8.70 | 0 | no | 0 | 0 | 0 |
| 16976 | 886-01 | 177.4 | 182.0 | 4.6 | 5.1 | 4.6 | 100 | 4E4 | 3.7 | 11.65 | 3.98 | 7.67 | 91.0 | 1.30 | 0.77 | 26.53 | 27.30 | 0 | np | 0 | 0 | 0 |
| 16977 | 886-01 | 182.0 | 186.5 | 4.5 | 4.7 | 4.5 | 100 | 4E4 | 4.3 | 26.32 | 9.62 | 16.70 | 154.0 | 1.17 | 1.17 | 24.33 | 25.50 | 0 | np | 0 | 0 | 0 |
| 16978 | 886-01 | 186.5 | 190.0 | 3.5 | 5.0 | 3.5 | 100 | 4E4 | 4 | 28.10 | 11.30 | 16.80 | 177.0 | 1.30 | 3.56 | 16.04 | 19.60 | 0 | np | 0 | 0 | 0 |
| 16979 | 886-01 | 190.0 | 194.7 | 4.7 | 6.6 | 4.7 | 100 | 4E4 | 3.9 | 28.90 | 11.40 | 17.50 | 165.0 | 1.75 | 4.27 | 16.53 | 20.80 | 0 | no | 0 | 0 | 0 |
| 16956 | 886-03 | 166.3 | 169.0 | 2.7 | 1.4 | 1.4 | 52 | 4E8 | 3.8 | 5.57 | 2.83 | 2.74 | 35.0 | 0.51 | 15.00 | 18.90 | 33.90 | 0 | np | 0 | 0 | 0 |
| 16957 | 886-03 | 169.0 | 172.0 | 3.0 | 4.4 | 3.0 | 100 | 4L24 | 3.1 | 4.95 | 2.32 | 2.63 | 33.0 | 0.21 | 6.72 | 12.48 | 19.20 | 0 | no | 0 | 0 | 0 |
| 16958 | 886-03 | 172.0 | 175.5 | 3.5 | 4.3 | 3.5 | 100 | 4E0 | 4.5 | 11.46 | 6.94 | 4.52 | 94.0 | 0.96 | 0.85 | 28.05 | 28.90 | 0 | np | 0 | 0 | 0 |
| 16960 | 886-03 | 272.9 | 276.1 | 3.2 | 3.9 | 3.2 | 100 | 4B0 | 4.3 | 23.77 | 8.87 | 14.90 | 131.0 | 0.82 | 1.41 | 19.49 | 20.90 | 0 | np | 0 | 0 | 0 |
| 16961 | 886-03 | 276.1 | 279.5 | 3.4 | 4.2 | 3.4 | 100 | 4G0 | 4.4 | 14.68 | 5.25 | 9.43 | 83.0 | 1.71 | 2.76 | 21.54 | 24.30 | 0 | np | 0 | 0 | 0 |
| 16962 | 886-03 | 279.5 | 280.5 | 1.0 | 2.5 | 1.0 | 100 | 4A0 | 2.8 | 5.38 | 0.56 | 4.82 | 14.0 | 0.27 | 3.27 | 7.23 | 10.50 | 0 | np | 0 | 0 | 0 |
| 16970 | 886-03 | 417.2 | 421.0 | 3.8 | 2.9 | 2.9 | 76 | 4E1 | 3.8 | 5.56 | 2.41 | 3.15 | 34.0 | 0.21 | 18.00 | 17.10 | 35.10 | 0 | np | 0 | 0 | 0 |

* Note : Recovery is measured as the total interval occupied by the core as it lies in the core box.
 Recovery has been adjusted in the ACT REC column to correct the intervals where measured core recovery is greater than the drilled interval.
 This occurs when the recovered core has been spread out in the core box.