

RECEIVED OCT 23 1989

006542

LAKEFIELD RESEARCH

185 Concession Street
Postal Bag 430
Lakefield, Ontario
K0L 2H0

Facsimile No. (705) 652-6365
Telephone No. (705) 652-3341

To: Mr. G. McDonald

Company: Cerrogh Resources

From: S. Bulatovic

Fax No.: 416 - 363 - 7111

Date: Oct 23, 1989

Reference: G-3 Composite Preparation

This transmission consists of 4 page(s), including this one.

Dear Godfrey:

Enclosed please find the Compositing procedure of Composite G3 as we discussed on Friday.

In order to make Composite with predicted grades we separate ores into high grade and low grade. Then we use 33.3% high grade and 66.7% low grade to make Composite assaying 4.3% Pb and 7.4% Zn. With this method all samples are represented and the head is close to average.

Regards - S. Bulatovic

opposite G-3 - High Grade (Cont'd)

Sample No.	Weight Kg	Assay %		M.U.	
		Pb	Zn	Pb	Zn
1157	4.338 (1/2) 2.169	7.33	18.3	15.90	39.69
1158	4.232	3.95	10.6	16.72	44.86
1159	3.970 (1/2) 1.985	6.25	16.6	12.41	32.95
1160	4.140	6.07	12.7	25.13	52.58
1161	2.243	6.35	11.4	19.24	29.57
Total	183.223	6.46	11.91	1183.96	2182.64

opposite G-3 - High Grade Samples

Sample No.	Weight		Assay %		M.U.	
	Kg.	Reduce to	Pb	Zn	Pb	Zn
067	2.542		5.04	10.6	12.81	26.95
068	3.744		5.05	9.18	18.91	34.37
070	1.812		9.79	19.8	17.74	35.88
071	2.473	(1/2) 1.236	8.07	15.9	19.97	19.65
072	4.385		4.51	8.36	19.78	36.66
073	3.810	(1/4) 1.905	12.4	24.3	23.62	46.29
077	7.652		5.62	11.8	43.00	90.29
078	9.900		6.78	10.4	67.12	102.96
079	9.035		7.16	9.65	64.69	87.19
080	8.121	(1/2) 4.061	8.54	14.0	34.68	56.85
081	8.158	(1/2) 4.079	8.70	14.2	35.49	57.92
082	2.024	(1/2) 1.012	7.69	20.1	17.78	20.34
083	6.162		6.78	11.7	41.78	72.10
084	4.794		6.38	13.5	30.59	64.72
085	3.323	(1/2) 1.661	8.77	18.6	14.57	30.89
086	6.204		4.70	11.4	29.16	70.73
087	6.681		5.53	13.8	36.95	92.20
088	6.404	(1/2) 3.202	8.95	17.2	28.66	55.07
089	5.200		6.94	13.2	36.09	68.64
090	6.030		6.71	13.0	40.46	78.39
091	6.557		8.21	12.1	53.83	79.34
092	5.417		5.79	10.3	31.36	55.80
094	7.358		6.81	10.0	50.11	73.58
095	5.172	(1/2) 2.586	9.51	16.8	24.59	43.44
096	5.480		6.60	9.18	36.17	50.31
097	4.103		6.55	11.9	26.87	48.83
145	4.958	(1/2) 2.479	7.87	11.3	19.51	28.01
146	5.363		5.57	11.5	29.87	61.67
147	3.737		5.96	13.4	22.27	50.08
1148	3.109		6.42	13.8	19.96	42.90
1149	2.506	(1/2) 1.253	7.82	20.2	9.80	25.31
1150	7.021		6.46	10.2	45.36	71.61
1151	9.147		5.19	9.13	47.47	83.51
1152	6.002		5.70	8.99	34.21	53.96
1153	7.545		4.55	9.35	34.33	70.55

