

MET LAB TEST COMPARISON

Cyprus Anvil
006965

PROJECT CONDITIONING BY SIZE 2BCD ore

| TEST Nb | %Pb Rec | LEAD | | SILVER | | | ZINC | | | REMARKS |
|------------|-------------------------|------|---|--------|----|---|------|----|---|--|
| | | AR | K | REC | AR | K | REC | AR | K | |
| - | 12 | | | | | | | | | 2-BCD ROUGHER TESTS (LEAD) |
| 13 | 92 | 0 | | | | | | | | STANDARD |
| 3 | 91 | -1 | | | | | | | | Condition by size / ^{Cond} 5min / 15min GRIND |
| 4 | 87 | -5 | | | | | | | | Parallel / " / " |
| 5 | 92 | 0 | | | | | | | | Condition by size / 2.5min / " |
| 6 | 92 | 0 | | | | | | | | Parallel / " / " |
| 7 | 87 | -5 | | | | | | | | Condition by size / ^{Cond} 4 min / 16 1/2 min GRIND |
| 8 | 87 | -5 | | | | | | | | Parallel / " / " |
| 9 | 86 | -6 | | | | | | | | Condition by size / " / 15min Grind / 50% Z-11 |
| 10 | 85 | -7 | | | | | | | | Parallel / " / " / " |
| | ^{Rec} 60%Pb | | | | | | | | | 2-BCD CLEANER TESTS (LEAD) |
| 20 | 76 | 0 | | | | | | | | STANDARD |
| 21 | 81 | +5 | | | | | | | | Cond by Size / ^{Cond} 5min / Normal grind / reagent |
| | | | | | | | | | | 2BCD Rougher tests (ZINC) |
| 13 | | | | | | | 76 | 0 | | STANDARD |
| 14 | | | | | | | 78 | +2 | | Cond by size / ^{Cond} 8min / Normal Reagents |
| 15 | | | | | | | 78 | +2 | | Parallel / 8 / " |
| 16 | | | | | | | 75 | -1 | | Cond by Size / 6 / " |
| 17 | | | | | | | 78 | +2 | | Parallel / 6 / " |
| 18 | | | | | | | 73 | -3 | | Cond by Size / 4 / " |
| 19 | | | | | | | 78 | +2 | | Parallel / 4 / " |
| 22 | | | | | | | 82 | +6 | | Cond. by Size / 8 / +50% Z-11 |
| 23 | | | | | | | 77 | +1 | | Parallel / 8 / +50% Z-11 |
| 24 | | | | | | | 77 | +1 | | Cond. by Size / 8 / Repeat 14 |
| 25 | | | | | | | 73 | -3 | | Parallel / 8 / Repeat 15 |

MET LAB TEST COMPARISON

PROJECT CONDITIONING BY SIZE — 2EF ore

| TEST Nb | LEAD | | | SILVER | | | ZINC | | | REMARKS |
|------------|------|-----|---|--------|----|---|------|----|---|---------------------------------------|
| | Rec | -AR | K | REC | AR | K | REC | AR | K | |
| | | | | | | | | | | 2EF ROUGHER TESTS (LEAD) |
| 1 | 94 | 0 | | | | | | | | STANDARD |
| 2 | 96 | +2 | | | | | | | | Cond by Size / Cond / Normal Reagents |
| 3 | 94 | 0 | | | | | | | | Parallel / " / " |
| 4 | 94 | 0 | | | | | | | | Cond by Size / 2.5 / " |
| 5 | 84 | -10 | | | | | | | | Parallel / 2.5 / " |
| | | | | | | | | | | 2EF ROUGHER TESTS (ZINC) |
| 1 | 84 | 0 | | | | | | | | STANDARD / Cond / Normal Reagents |
| 6 | 87 | +3 | | | | | | | | Cond by Size / 8 / " |
| 7 | 89 | +5 | | | | | | | | Parallel / 8 / " |
| 8 | ? | - | | | | | | | | Cond. by Size / 6 / " |
| 9 | ? | - | | | | | | | | Parallel / 6 / " |
| 10 | 84 | 0 | | | | | | | | Cond by Size / 8 / +50% Z-11 |
| 11 | ? | - | | | | | | | | Parallel / 8 / +50% Z-11 |