

007230

URGENT! AS SOON AS POSSIBLE 13423

FROM

Peter Ledwidge

DEPT.

Geology

COPY TO

D. Tenney D. Tuliv.

SEND TO

Gordon Wilson
Chief Metallurgist

DATE

SUBJECT

MESSAGE

Samples taken - week of Jan 07 - 11/91

90-PL-23 - 2 buckets 0-3/4", 2 buckets 3/4"-8" for floatation tests [Refractory ore from Pelley screen plant (New pile)] Results - Good floatation when mixed 25/75% w/ Favo ore.

90-PL-24 - 2 buckets 0-3/4" from old Pelley screen stockpile for density tests - Results - 1.91

90-PL-25 - 2 buckets 0-3/4" from new Pelley screen stockpile for density tests - Results 2.13

REPLY

4S500E - 1

← SPEEDIMEMO →

MOORE SPEEDILY - 1 - MOORE CLEAN PRINT PATENTED 1963-1966

REPLY
FROM

DATE

LIFT THIS SHEET TO REMOVE
(RETAIN FOR YOUR FOLLOW-UP)