014461 Cop GP

Rosby Tungsten
Summary description

The west zone, approximately 20' x 400' showed values ranging between 0.18% and 4.21% WO_3 over the entire showing. The best section had an average assay of 1.24% WO_3 over 25.0', while the average unweighted assay on the west zone was .83% WO_3.

The east showing which is intermittently overburden covered is approximately 20 feet thick and 3500 feet long. Three sections over 1300' in an area of good exposure assayed .67% WO_3 over 25', .58% WO_3 over 25' and .63% WO_3 over 30'. Two grab samples between these sections ran .16% WO_3 and .46% WO_3. The average unweighted assay of 64 samples collected on the east zone was .46% WO_3.

0.46

0.58
67
63
3) 188
63

Bar 6P

6231' total

Zinc mineralization occurs on the Bay Mineral Claims in varying amounts in a thick sequence of interbedded black shales, dolomitic shales and silicified dolomites. The mineralogy is simple, consisting of sphalerite, pyrite, minor galena in a gangue of quartz, calcite, dolomite, siderite and minor gypsum. The sphalerite has two distinct types of occurrence; As narrow open space filling veinlets and as trace disseminated replacements. Although zinc mineralization was intersected in almost every hole, ~~sections of economic grade~~ significant values were obtained in only 5 holes.

The widths and average assays are as follows:

PDDH 68-2a	30 feet @	2.20% Zn
PDDH 68-7	23 feet @	2.77% Zn
PDDH 68-15	15 feet @	3.41% Zn
~~PDDH 68-15~~	16 feet @	2.9% Zn
	4 feet @	4.5% Zn
PDDH 68-19	13.8 feet @	4.6% Zn
PDDH 68-20	18 feet @	2.9% Zn