

.74
 .68
 .60
 .37
 .64
 3.03
 5

~~A1 GAMES~~

MAIN SITOWING

CHIP.	CNTURB.	C-E.
A1 CHIP.	.74	.67
A2 CHIP.	.68	.58
A3 CHIP.	.60	.63
AA CHIP.	.37	.19
AS CHIP.	.64	.23

.67
 .58
 .63
 .19
 .23
 2.30
 5

WEST SITOWING

LINE 1 CHIP.	1.15	1.24
2	.41	.48
3	.59	.76

Average grade indicated from preliminary chip sampling
 and ~~chip~~ assay by X Ray techniques is .61%
 tungsten across widths of about 20 feet. ~~Selected~~
~~Chip~~ sampling assays of grab samples run as high
 as 7.37% tungsten.