

DATE June 18th 1962

FILE NO. II88-29

ASSAY CERTIFICATE

014873

WHITEHORSE ASSAY OFFICE

P. O. BOX 346, WHITEHORSE, YUKON

RECEIVED FROM Silver Titan Mines Ltd. Dr. A. E. Aho

YUKONO

SAMPLE No.

GOLD
OZ. PER TONSILVER
OZ. PER TON

Lead

Zinc

width

Location:
Surface -

S - 1

60.4

40.5

9.5

1.0'

5' N.

- 2

60.4

16.7

12.8

0.5'

10' N

- 3

110.1

41.3

6.7

3.5'

39.5' N

- 4

64.6

32.8

.6

2.5'

45.0 N

- 5

44.7

21.9

8.4

2.5'

50.0 N

- 6

63.3

16.0

2.8

1.5'

55.5 N

- 7

270.0

49.3

Float.

60.0 N

- 8

133.8

67.7

"

pit 19' S.

- 9

99.7

36.4

5.2

1.0'

N wall 9' depth

- 10

71.1

27.8

14.4

1.0'

N wall 14' " N wall.

- 11

8.8

3.1

4.0

3.5'

FW @ 14'

- 12

5.10

0.8

1.3

3.5'

FW @ 9' S side

- 13

14.6

6.8

25.6

1.9'

HW (Zinc)

- 14

18.4

2.5

2.5'

pyrite above HW

- 15

45.8

23.2

25.8

3.1'

HW } S side # 2 shaft

- 16

7.70

0.6

2.5

2.9'

FW

ASSAYER

Geo. Spalding

DATE June 18th 1962FILE NO. 1188-20

ASSAY CERTIFICATE

WHITEHORSE ASSAY OFFICE

P.O. BOX 346, WHITEHORSE, YUKON

RECEIVED FROM Silver Titan Mines Ltd., Dr. A.E. Aho

SAMPLE No.	GOLD OZ. PER TON	SILVER OZ. PER TON	Lead	Zinc				
S - 17		34.9	24.0	12.1	3.2'	Hw - N. side #2 Shaft.		
- 18		2.34	0.4	2.1	2.1'			
- 19		158.7	76.7		Galena with #17			
- 20		182.2	80.0		Galena from pit below road.			

ASSAYER

Geo Spelling