

Book 1

GRUM PROJECT
UNDERGROUND
D. DRILLING

014939

• ASSAYS. & INTERSECTIONS.

• U-1 - U-93 •



BOOK N^o 1

GRUM PROJECT.

VANGORDA CREEK.

Y.T.

UNDERGROUND, DIAMOND DRILLING

ASSAYS & SECTIONS.

DDH # U. 1

/o

DDH # U. 93

1.12.75 - 3.12.75

LATITUDE. 10778.51 N.

DIP AT COLLAR. +3°

DEPARTURE 7691.93 E

BEARING. N. 110° 13' 11"

ELEVATION. 1154.6 M.

DEPTH 62.5 M. (205 ft.)

ASSAY NUMBER	SECTION		CORE LENGTH (M)	ASSAYS		
	FROM	TO		Ag. ozs	Pb %	Zn %
1101	0.00 ✓	2.00 ✓	2.0	1.62	3.98 ✓	5.89 ✓
1102	2.0 ✓	4.00 ✓	2.0	1.59	4.17 ✓	4.60 ✓
1103	4.0 ✓	6.00 ✓	2.0	1.82	4.28 ✓	6.45 ✓
1104	6.0 ✓	8.00 ✓	2.0	1.85	4.05 ✓	9.45 ✓
1105	8.0 ✓	9.00 ✓	1.0	1.68	4.09 ✓	6.90 ✓
	9.0 ✓	14.0 ✓	5.0	NOT ASSAYED		
1106	14.00 ✓	15.00 ✓	1.0	3.77	9.26 ✓	15.00 ✓
1107	15.0 ✓	17.30 ✓	2.3	1.62	3.38 ✓	10.46 ✓
1108	17.3 ✓	18.80 ✓	1.5	3.24	8.50 ✓	17.22 ✓
	18.8 ✓	44.1 ✓	25.3	NOT ASSAYED		
1109	44.10 ✓	45.70 ✓	1.6	4.06 ✓	8.35 ✓	12.52 ✓
1110	45.7 ✓	47.20 ✓	1.5	3.38 ✓	8.15 ✓	14.81 ✓
1111	47.2 ✓	48.80 ✓	1.6	3.18 ✓	6.79 ✓	13.74 ✓
1112	48.8 ✓	50.30 ✓	1.5	2.85 ✓	7.56 ✓	12.16 ✓
	50.3 ✓	51.8 ✓	1.5	NOT ASSAYED		
1113	51.80 ✓	53.30 ✓	1.5	4.81 ✓	7.99 ✓	10.07 ✓
1114	53.3 ✓	54.90 ✓	1.6	3.77 ✓	8.85 ✓	14.60 ✓
	54.9 ✓	62.5 ✓	7.6	0.00	0.00	0.00

End of hole

44.1 m - 50.3 m = 6.2 m (20.3 ft)

Ag 3.38 ozs

Pb 7.7%

Zn 13.3%

44.1 m - 54.9 m = 10.8 m (35.43 ft)

Ag 3.16 ozs

Pb 6.85%

Zn 11.20%

51.8 m - 54.9 m = 3.1 m (10.17 ft)

Ag 4.27 ozs Pb 8.43%

Zn 12.41%

E.C.J.

4.12.75 - 5.12.75

ASSAY NUMBER	SECTION		CORE LENGTH (M)	ASSAYS		
	FROM	TO		Ag. ogs	Pb %	Zn %
1115	0.00 ✓	1.20 ✓	1.2	1.85	4.73 ✓	7.63 ✓
1114	1.2 ✓	2.50 ✓	1.3	1.65	4.20 ✓	6.64 ✓
1117	2.5 ✓	3.40 ✓	0.9	1.65	4.50 ✓	5.70 ✓
1118	3.4 ✓	4.40 ✓	1.0	1.41	3.30 ✓	7.81 ✓
1119	4.4 ✓	6.20 ✓	1.8	2.47	5.18 ✓	9.77 ✓
1120	6.2 ✓	8.40 ✓	2.2	1.47	3.00 ✓	6.98 ✓
	8.4 ✓	50.3 ✓	41.9	0.00	0.00	0.00

End of hole

LATITUDE 10779.73 N.

DIP AT COLLAR +3°

DEPARTURE 7691.53 W.

BEARING 56° 20' 02"

ELEVATION 1154.66 M.

DEPTH 50.3 M. (165.03 ft)

0.0 m - 8.4 m = 8.4 m (27.56 ft)

Ag 1.78 ogs.

Pb 4.10 %

Zn 7.58 %

E.C.J.

6.12.75 - 10.12.75

ASSAY NUMBER	SECTION		CORE LENGTH(M)	ASSAYS		
	FROM	TO		Ag ggs	Pb %	Zn %
1121	0.00 ✓	1.00 ✓	1.0	0.68	1.88 ✓	2.10 ✓
1122	1.00 ✓	3.00 ✓	2.0	1.15	3.30 ✓	5.25 ✓
1123	3.0 ✓	5.00 ✓	2.0	1.06	3.68 ✓	5.00 ✓
1124	5.0 ✓	7.00 ✓	2.0	1.82	5.15 ✓	6.35 ✓
1125	7.0 ✓	7.80 ✓	0.8	1.59	3.98 ✓	4.00 ✓
1126	7.8 ✓	8.90 ✓	1.1	2.12	4.43 ✓	8.95 ✓
1127	8.9 ✓	11.90 ✓	3.0	1.03	1.65 ✓	1.30 ✓
1128	11.9 ✓	14.30 ✓	2.4	0.83	1.50 ✓	2.05 ✓
1129	14.3 ✓	16.00 ✓	1.7	4.62	10.08 ✓	19.27 ✓
	16.0 ✓	42.7 ✓	26.7	NOT	ASSAYED	
1130	42.70 ✓	43.50 ✓	0.8	3.00 ✓	7.95 ✓	6.82 ✓
1131	43.5 ✓	45.50 ✓	2.0	2.76	6.82 ✓	5.00 ✓
1132	45.5 ✓	47.50 ✓	2.0	2.65	6.71 ✓	5.00 ✓
1133	47.5 ✓	49.00 ✓	1.5	3.72 ✓	11.40 ✓	6.52 ✓
1134	49.0 ✓	51.80 ✓	2.8	0.59	1.73 ✓	1.55 ✓
1135	51.8 ✓	52.80 ✓	1.0	0.74	1.95 ✓	1.82 ✓
	52.8 ✓	64.0 ✓	11.2	NOT	ASSAYED	
1601	64.00 ✓	65.40 ✓	1.4	0.48	1.00 ✓	1.30 ✓
1602	65.4 ✓	66.70 ✓	1.3	2.84 ✓	7.04 ✓	5.65 ✓
	66.7 ✓	72.4 ✓	5.7	NOT	ASSAYED	
1136	72.40 ✓	74.10 ✓	1.7	1.44	3.68 ✓	2.90 ✓
	74.1 ✓	82.3 ✓	8.2	0.00	0.00	0.00

End of hole

NOV

LATITUDE 10717.12
 DEPARTURE 10720.19
 ELEVATION 1157.62

DIP AT COLLAR +38°
 BEARING 225° 03' 23"
 DEPTH 82.3 m (270.0 ft)

1.0m - 8.9m = 7.9m (25.9 ft)

Ag 1.48 ggs

Pb 4.09 %

Zn 5.85 %

0.0m - 16.0m = 16.0m (52.5 ft)

Ag 1.58 ggs

Pb 3.74 %

Zn 5.62 %

14.3m - 16.0m = 1.7m (5.6 ft) Ag 4.62 ggs Pb 10.08 % Zn 19.27 %

42.7m - 49.0m = 6.3m (20.67 ft)

Ag 2.98 ggs

Pb 7.86 %

Zn 5.59 %

42.7m - 52.8m = 10.1m (33.14 ft)

Ag 2.10 ggs

Pb 5.38 %

Zn 4.10 %

64.0m - 66.7m = 2.7m (8.86 ft)

Ag 1.62 ggs Pb 3.91 %

Zn 3.39 %

E.C.J.

10.12.75 - 17.12.75.

ASSAY NUMBER	SECTION		CORE LENGTH (M)	ASSAYS.		
	FROM	TO		Ag %	Pb %	Zn %
	0.0	6.9	6.9	0.00	0.00	0.00
1603	6.90	10.60	3.7	1.29	2.98	4.95
1604	10.6	14.26	3.6	1.23	2.68	4.63
1605	14.2	14.90	0.7	0.61	1.13	2.10
1606	14.9	15.50	0.6	1.26	2.40	3.80
1151	15.5	17.50	2.0	4.47	10.31	17.51
1152	17.5	19.00	1.5	4.21	9.81	17.25
	19.0	45.7	26.7	NOT ASSAYED		
1153	45.70	46.20	0.5	0.88	2.70	2.50
1154	46.2	47.80	1.6	3.68	9.70	6.72
1155	47.8	48.70	0.9	0.80	2.25	1.49
	48.7	53.3	4.6	0.00	0.00	0.00

End of hole.

LATITUDE 10420.9
 DEPARTURE 7631.53
 ELEVATION 1155.62m

DIP AT COLLAR +75°
 BEARING 235° 31' 10"
 DEPTH 53.3m

6.9m - 19.0m = 12.1m (42.3ft)

Ag 2.12%

Pb 4.81%

Zn 8.25%

15.5m - 19.0m = 3.5m (11.48ft)

Ag 4.36% Pb 10.10% Zn 17.40%

45.7m - 48.7m = 3.0m (9.84ft)

Ag 2.35% Pb 6.30%

Zn 4.40%

E.O.J.

DDH U. 5 ✓

14.12.75 - 16.12.75

ASSAY NUMBER	SECTION		CORE LENGTH (M)	ASSAYS		
	FROM	TO		Ag ops	Pb%	Zn%
	0.0	27.4	27.4			
1007	27.4	28.4	1.0	1.55	2.70	3.88
1137	28.4	30.4	2.0	2.24	6.03	11.86
1138	30.4	32.4	2.0	0.94	1.55	2.50
1139	32.4	34.0	1.6	2.38	4.80	10.85
	34.0	34.9	0.9	NOT ASSAYED		
1140	34.9	37.7	2.8	1.68	3.53	6.72
	37.7	40.5	2.8	NOT ASSAYED		
1008	40.5	43.8	3.3	1.51	2.95	5.93
1009	43.8	44.6	0.8	4.19	3.40	4.80
1010	44.6	46.4	1.8	1.10	2.30	4.10
1011	46.4	48.8	2.4	0.78	1.43	3.53
1318	48.8	50.2	1.4	1.35	2.80	5.93
1319	50.2	52.2	2.0	2.03	4.55	10.04
1320	52.2	54.2	2.0	1.88	3.90	8.50
1141	54.2	56.2	2.0	2.59	5.10	9.47
1142	56.2	58.2	2.0	2.21	4.05	6.56
1143	58.2	60.2	2.0	1.56	3.53	4.15
1144	60.2	62.2	2.0	0.91	1.93	3.20
1145	62.2	64.2	2.0	3.15	7.04	12.21
1146	64.2	66.2	2.0	3.18	6.53	12.57
1147	66.2	68.2	2.0	2.00	4.13	6.92
1148	68.2	70.2	2.0	3.79	8.17	21.13
1149	70.2	72.2	2.0	2.74	7.05	9.77
1150	72.2	74.2	2.0	0.56	1.73	3.27
	74.2	99.1	24.9	0.00	0.00	0.00

End of hole

LATITUDE 10720.45
 DEPARTURE 7632.27
 ELEVATION -1151.62 m

DIP AT COLLAR -90°
 BEARING.
 DEPTH 99.1 m (325.13 ft)

27.4 - 34.0 = 6.6 m (21.65 ft)

Ag 1.78 ops

Pb 3.95%

Zn 7.51%

27.4 - 44.2 = 16.8 m (53.54 ft)

Ag 1.79 ops

Pb 3.75%

Zn 7.09%

50.2 - 56.2 = 6.0 m (19.7 ft)

Ag 2.17 ops Pb 4.39 ops

Zn 9.34 ops

62.2 - 66.2 = 4.0 m (13.12 ft)

Ag 3.17 ops Pb 6.79% Zn 12.39%

68.2 - 72.2 = 4.0 m (13.12 ft)

Ag 3.27 ops Pb 7.61% Zn 15.45%

E.C.J.

17.12.75 - 19.12.75

ASSAY NUMBER	SECTION		CORE LENGTH(M)	ASSAYS		
	FROM	TO		Ag ogs	Pb %	Zn %
1612	0.0 ✓	2.4 ✓	2.4	1.29	2.85 ✓	3.65 ✓
1156	2.4 ✓	4.6 ✓	2.2	0.97	2.30 ✓	4.70 ✓
1157	4.6 ✓	6.0 ✓	1.4	0.80	1.95 ✓	3.75 ✓
1613	6.0 ✓	9.1 ✓	3.1	1.10	2.28 ✓	4.58 ✓
1158	9.1 ✓	11.1 ✓	2.0	1.18	3.08 ✓	5.40 ✓
1159	11.1 ✓	14.3 ✓	3.2	1.03	3.08 ✓	4.65 ✓
1614	14.3 ✓	15.2 ✓	0.9	0.45	0.95 ✓	2.70 ✓
1615	15.2 ✓	18.5 ✓	3.3	1.10	1.93 ✓	3.65 ✓
1616	18.5 ✓	19.5 ✓	1.0	1.13	1.78 ✓	3.50 ✓
1617	19.5 ✓	21.2 ✓	1.7	2.03	3.78 ✓	6.85 ✓
1618	21.2 ✓	21.8 ✓	0.6	2.64	4.83 ✓	7.50 ✓
1160	21.8 ✓	23.8 ✓	2.0	6.18 ✓	13.55 ✓	26.10 ✓
1161	23.8 ✓	25.9 ✓	2.1	5.15 ✓	11.34 ✓	22.17 ✓
1162	25.9 ✓	28.0 ✓	2.1	1.47	2.93 ✓	5.85 ✓
1163	28.0 ✓	30.0 ✓	2.0	4.71 ✓	9.32 ✓	17.82 ✓
1164	30.0 ✓	32.0 ✓	2.0	3.74 ✓	8.42 ✓	14.00 ✓
1165	32.0 ✓	33.2 ✓	1.2	3.94 ✓	8.60 ✓	15.52 ✓
	33.2 ✓	36.6 ✓	3.4	0.00	0.00	0.00

End of hole

LATITUDE 10.779.91

DEPARTURE 1632.25

ELEVATION 1155.6 m

DIP AT COLLAR +80°

BEARING 45° 00' 00"

DEPTH 36.6 m (120 ft)

0.0 m - 33.2 m = 33.2 m (108.9 ft)

Ag 2.29 ogs

Pb 4.79 %

Zn 8.78 %

21.8 - 25.9 = 4.1 m (13.5 ft)

Ag 5.65 ogs Pb 12.42 % Zn 24.08 %

28.0 - 33.2 = 5.2 m (17.1 ft)

Ag 4.65 ogs Pb 8.83 %

Zn 15.82 %

(E.C.)

19.12.75 - 23.12.75

ASSAY NUMBER	SECTION		CORE LENGTH (M)	ASSAYS		
	FROM	TO		Ag %	Pb %	Zn %
1619	0.0 ✓ 10.7 ✓	10.7 ✓ 11.2 ✓	10.7 0.5	0.00 1.48	0.00 3.40	0.00 1.53
1166	11.2 ✓	13.2 ✓	2.0	1.53	4.65	1.98
1167	13.2 ✓	15.2 ✓	2.0	1.47	3.85	2.60
1620	15.2 ✓	19.8 ✓	4.6	1.45	2.93	2.43
1621	19.8 ✓	21.4 ✓	1.6	0.29	0.39	0.90
1622	21.4 ✓	23.0 ✓	1.6	0.35	0.68	1.00
1168	23.0 ✓	24.8 ✓	1.8	1.18	2.70	3.65
	24.8 ✓	32.0 ✓	7.2	NOT ASSAYED		
1623	32.0 ✓	35.0 ✓	3.0	0.91	1.65	2.45
1624	35.0 ✓	35.7 ✓	0.7	1.81	3.38	5.09
	35.7 ✓	53.8 ✓	18.1	NOT ASSAYED		
1169	53.8 ✓	54.7 ✓	0.9	3.74	7.39	12.72
1170	54.7 ✓	56.1 ✓	1.4	1.29	3.00	4.00
	56.1 ✓	73.2 ✓	17.1	0.00	0.00	0.00

End of hole

LATITUDE 10746.7

DIP AT COLLAR -60°

DEPARTURE 7652.8

BEARING 44°

ELEVATION 1151.8

DEPTH 73.2 m, 240.12 ft

11.2-15.2 = 4.0m (13.12 ft)

LOW

Ag 1.50% Pb 4.25% Zn 2.29%

35.0-35.7 = 0.7m (2.3 ft) Ag 1.81% Pb 3.38% Zn 5.09%

53.8-56.1 = 2.3m (7.6 ft)

Ag 2.25% Pb 4.72% Zn 7.41%

24.12.75 - 27.12.75

ASSAY NUMBER	SECTION		CORE LENGTH (M)	ASSAYS		
	FROM	TO		Ag %	Pb %	Zn %
1171	0.0	30.5	30.5	0.00	0.00	0.00
	30.5	31.9	1.40	0.97	2.35	2.35
	31.9	32.7	0.8	NOT ASSAYED		
1172	32.7	34.2	1.50	1.32	3.60	3.90
	34.2	34.7	0.5	NOT ASSAYED		
1173	34.7	36.2	1.50	1.27	3.45	6.30
	36.2	36.7	0.5	NOT ASSAYED		
1174	36.7	38.7	2.00	0.85	1.65	3.50
1175	38.7	40.9	2.2	0.71	1.50	2.60
1176	40.9	42.9	2.00	3.09	8.37	16.26
1177	42.9	43.9	1.00	3.09	6.54	12.95
	43.9	50.3	6.4	0.00	0.00	0.00

End of hole.

LATITUDE 10746.71
 DEPARTURE 7652.78
 ELEVATION 1155.87

DIP AT COLLAR +80°
 BEARING 218° 26' 35"
 DEPTH 50.3 m. (165 ft)

30.5 - 36.2 = 5.7 m (18.7 ft)
 Ag 0.92%
 Pb 2.43%
 Zn 3.26%
 LOW

40.9 - 43.9 = 3.0 m (10.0 ft)
 Ag 3.09%
 Pb 4.76%
 Zn 15.16%

(E.C.J.)

28.12.75 - 30.12.75

ASSAY NUMBER	SECTION		CORE LENGTH (M)	ASSAYS		
	FROM	TO		Ag ^{ags}	Pb %	Zn %
	0.0	4.5	4.5	0.00	0.00	0.00
1178	4.5	6.5	2.0	1.47	3.68	3.95
1179	6.5	8.5	2.0	0.97	2.28	3.20
1180	8.5	10.5	2.0	1.85	6.31	3.25
1181	10.5	12.5	2.0	1.53	4.88	7.48
1182	12.5	14.5	2.0	1.44	4.05	5.60
1183	14.5	16.5	2.0	1.29	3.68	4.75
1184	16.5	18.0	1.5	1.35	3.38	6.92
	18.0	22.3	4.3	NOT ASSAYED		
1185	22.3	24.3	2.0	0.85	1.83	4.40
1186	24.3	26.0	1.7	2.62	6.11	12.11
1187	26.0	27.0	1.0	4.09	9.70	12.52
	27.0	29.0	2.0	NOT ASSAYED		
1188	29.0	31.0	2.0	4.65	7.81	13.69
1625	31.0	32.0	1.0	1.13	2.10	2.00
1626	32.0	33.0	1.0	1.10	2.20	2.98
	33.0	38.1	5.1	NOT ASSAYED		
1627	38.1	39.5	1.4	0.13	0.33	1.10
1190	39.5	41.1	1.6	2.94	7.38	10.69
1191	41.1	42.7	1.6	3.38	7.54	12.93
1192	42.7	44.2	1.5	4.91	9.75	14.05
1193	44.2	45.4	1.2	1.53	3.38	7.23
1194	45.4	47.2	1.8	2.12	4.80	7.53
1195	47.2	48.7	1.5	2.18	5.03	6.10
1196	48.7	50.3	1.6	2.32	6.50	7.84
1197	50.3	51.2	0.9	3.00	6.50	10.69
1198	51.2	53.3	2.1	1.06	2.25	4.50
	53.3	64.0	10.7	0.00	0.00	0.00

LATITUDE 10765.6
 DEPARTURE 7671.8
 ELEVATION 1152 m

DIP AT COLLAR -55°
 BEARING 44°
 DEPTH 64.0 m (210 ft)

4.5 m - 18.0 m = 13.5 m (44.29 ft)
 Ag 1.42 ags.
 Pb 4.06 %
 Zn 4.95 %

22.3 - 27.0 = 4.7 m (15.41 ft)
 Ag 2.18 ags Pb 5.05 %
 Zn 8.92 %

4.5 m - 53.3 m = 48.8 m (160 ft)
 Ag 1.56 ags
 Pb 3.66 %
 Zn 5.48 %

29.0 - 31.0 = 2.0 m (6.56 ft)
 Ag 4.65 ags Pb 7.81 % 13.69 %

39.5 m - 53.3 m = 13.8 m (45.2 ft)
 Ag 2.54 ags
 Pb 5.78 %
 Zn 8.83 %

End of hole.

31.12.75 - 4.1.76

ASSAY NUMBER	SECTION		CORE LENGTH (M)	ASSAYS		
	FROM	TO		Ag μ g/g	Pb %	Zn %
1199	0.0	2.7	2.7	2.41	4.43	9.63
1200	2.7	4.3	1.6	1.47	2.85	4.75
1201	4.3	6.1	1.8	1.47	3.38	7.12
1202	6.1	7.6	1.5	1.38	3.08	7.43
1203	7.6	9.1	1.5	1.35	3.08	5.88
1204	9.1	10.7	1.6	3.18	6.74	8.91
1205	10.7	12.2	1.5	1.06	2.25	6.32
1206	12.2	13.7	1.5	0.09	0.37	0.94
1207	13.7	15.2	1.5	0.35	0.98	3.00
	15.2	40.4	25.2	NOT ASSAYED		
1208	40.4	41.1	0.7	4.68	11.69	15.98
1209	41.1	44.5	3.4	0.74	1.63	3.95
	44.5	50.4	5.9	NOT ASSAYED		
1210	50.4	52.5	2.1	0.62	1.05	1.60
	52.5	53.3	0.8	NOT ASSAYED		
1211	53.3	54.9	1.6	1.27	2.50	4.10
1213	54.9	56.4	1.5	1.44	3.30	5.90
1214	56.4	57.2	0.8	4.12	9.17	16.09
	57.2	64.0	6.8	0.00	0.00	0.00

End of hole

LATITUDE 10765.58
 DEPARTURE 4671.82
 ELEVATION 1158.41

DIP AT COLLAR + 77°
 BEARING 233° 47' 07"
 DEPTH 64.0m (210.0ft)

0.0m - 12.2m = 12.2m (40.03ft)

Ag 1.83 μ g/g
 Pb 3.77%
 Zn 7.38%

0.0m - 15.2m = 15.2m (49.87ft)

Ag 1.51 μ g/g
 Pb 3.16%
 Zn 6.30%

40.4m - 44.5m = 4.1m (13.45ft)

Ag 1.41 μ g/g Pb 3.35% Zn 6.00%

40.4m - 57.2m = 16.8m (55ft)

Ag 0.88 μ g/g
 Pb 1.92%
 Zn 3.35%

LOW

53.3m - 57.2m = 3.9m (12.8ft)

Ag 1.92 μ g/g Pb 4.18%
 Zn 7.25%

E.C.J.

4.1.76 - 5.1.76

ASSAY NUMBER	SECTION		CORE LENGTH(M)	ASSAYS		
	FROM	TO		Ag. gts	Pb %	Zn %
	0.0	5.3	5.3	0.00	0.00	0.00
1214	5.3	7.3	2.0	3.71	7.17	20.51
1215	7.3	9.3	2.0	1.82	3.60	12.04
	9.3	24.4	15.1	0.00	0.00	0.00

End of hole

LATITUDE 10781.47
 DEPARTURE 7694.46
 ELEVATION 1153.72
 DIP AT COLLAR -40°
 BEARING 26° 10'
 DEPTH 24.4 m (80 ft.)
 5.3m - 9.3m = 4.0m (13.12 ft)
 Ag. 2.77 gts Pb 5.39% Zn 16.28%

(E.C.I.)

5.1.76 - 6.1.76

ASSAY NUMBER	SECTION		CORE LENGTH (M)	ASSAYS		
	FROM	TO		Ag μ g/g	Pb μ g/g	Zn μ g/g
	0.0	15.7	15.7	0.00	0.00	0.00
1216	15.7	16.8	1.1	3.15	3.29	15.96
1217	16.8	18.0	1.2	1.44	2.85	4.75
1218	18.0	19.0	1.0	2.38	5.20	6.71
1219	19.0	20.7	1.7	2.35	5.18	7.28
1220	20.7	22.3	1.6	0.53	1.13	3.65
1221	22.3	23.7	1.4	3.18	5.48	7.50
1222	23.7	24.9	1.2	2.65	5.98	10.51
1223	24.9	26.1	1.2	2.41	6.20	10.12
1224	26.1	27.4	1.3	1.06	3.55	4.93
1225	27.4	28.7	1.3	1.68	3.85	5.50
	28.7	55.1	26.4	NOT ASSAYED		
1226	55.1	56.4	1.3	3.53	6.94	6.35
1227	56.4	57.9	1.5	2.94	7.06	11.03
1228	57.9	59.4	1.5	2.21	5.78	8.95
1229	59.4	61.0	1.6	1.32	3.00	4.65
1230	61.0	62.5	1.5	0.88	1.70	0.48
1231	62.5	64.0	1.5	0.29	0.15	0.28
1232	64.0	65.5	1.5	2.06	4.50	4.90
1233	65.5	67.0	1.5	2.47	6.33	5.35
1234	67.0	68.6	1.6	0.29	0.20	1.18
1235	68.6	70.1	1.5	0.29	0.05	0.88
1236	70.1	71.6	1.5	0.35	0.25	0.90
1237	71.6	73.1	1.5	0.32	0.25	2.00
1238	73.1	74.7	1.6	1.35	2.80	2.38
1239	74.7	76.2	1.5	0.29	0.45	6.51
	76.2	79.9	3.7	0.00	0.00	0.00

End of hole

LATITUDE 10685.91
 DEPARTURE 7600.5
 ELEVATION 1152.91

DIP AT COLLAR -70°
 BEARING 43° 47' 59"
 DEPTH 79.9 m (262 ft)

15.7 m - 28.7 m = 13 m (42.65 ft)

Ag 2.04 μ g/g
 Pb 4.71 μ g/g
 Zn 7.47 μ g/g

55.1 m - 67.0 m = 11.9 m (39.0 ft)

Ag 1.93 μ g/g
 Pb 4.39 μ g/g
 Zn 5.91 μ g/g

55.1 m - 76.2 m = 21.1 m (69.23 ft)

Ag 1.30 μ g/g
 Pb 2.77 μ g/g
 Zn 4.34 μ g/g

E.C.J.

7.1.76 - 10.1.76

ASSAY NUMBER	SECTION		CORE LENGTH	ASSAYS		
	FROM	TO		Ag. ^{ags}	Pb %	Zn %
	0.0	17.1	17.1	0.00	0.00	0.00
1240	17.1	18.3	1.2	2.09	5.20	6.86
1241	18.3	19.8	1.5	3.27	7.26	11.03
1242	19.8	21.3	1.5	2.94	6.84	7.96
1243	21.3	22.9	1.6	2.15	4.30	4.20
1244	22.9	24.4	1.5	1.84	4.40	5.62
1245	24.4	25.9	1.5	2.18	4.60	6.51
1246	25.9	27.9	2.0	3.82	10.03	14.69
	27.9	55.2	27.3	NOT ASSAYED		
1247	55.2	56.4	1.2	2.82	6.61	8.98
1248	56.4	57.9	1.5	2.06	4.40	5.25
1249	57.9	59.5	1.6	2.88	6.94	8.55
1250	59.5	62.5	3.0	1.59	3.50	2.95
1251	62.5	64.0	1.5	0.26	0.15	0.53
1252	64.0	65.5	1.5	1.44	2.85	0.78
1253	65.5	67.1	1.6	0.29	0.20	1.03
1254	67.1	68.6	1.5	0.32	0.35	1.10
1255	68.6	70.1	1.5	2.18	4.60	2.03
1256	70.1	71.6	1.5	1.24	3.10	3.48
	71.6	77.4	5.8	NOT ASSAYED		
1257	77.4	78.2	0.8	4.41	11.06	17.37
	78.2	157.2	79.0	NOT ASSAYED		
1258	157.2	158.5	1.3	0.91	2.40	2.28
1259	158.5	160.0	1.5	1.32	3.85	3.15
1260	160.0	161.5	1.5	1.71	5.25	3.75
	161.5	178.0	16.5	NOT ASSAYED		
1261	178.0	179.8	1.8	1.00	2.00	0.88
	179.8	182.9	3.1	0.00	0.00	0.00

End of hole

LATITUDE 10685.48
 DEPARTURE 7600.08
 ELEVATION 1152.91

DIP AT COLLAR -83°
 BEARING 43° 47' 59"
 DEPTH 182.9 m (600 ft)

17.1 m - 27.9 m = 10.8 m (34.4 ft)

Ag 2.68 ags
 Pb 6.28 %
 Zn 8.42 %

55.2 m - 62.5 m = 7.3 m (24 ft)

Ag 2.17 ags
 Pb 4.95 %
 Zn 5.64 %

55.2 - 71.6 = 16.4 m (53.8 ft) low

Ag 1.49 ags
 Pb 3.23 %
 Zn 3.39 %

77.4 m - 78.2 m = 0.8 m (2.62 ft)

Ag 4.41 ags
 Pb 11.06 %
 Zn 17.37 %

158.5 m - 161.5 m = 3.0 m (9.84 ft)

Ag 1.52 ags
 Pb 4.55 %
 Zn 3.45 %

11.1.76 - 12.1.76

ASSAY NUMBER	SECTION		CORE LENGTH (M)	ASSAYS		
	FROM	TO		Ag ops	Pb %	Zn %
	0.0 ✓	19.5 ✓	0.0 19.5	0.00	0.00	0.00
1262	19.5 ✓	20.1 ✓	0.6	3.82 ✓	10.69 ✓	9.88 ✓
1263	20.1 ✓	21.7 ✓	1.6	1.44	3.85 ✓	2.15 ✓
1264	21.7 ✓	23.5 ✓	1.8	0.91	0.48 ✓	0.13 ✓
1265	23.5 ✓	24.9 ✓	1.4	2.71	6.47 ✓	6.49 ✓
1266	24.9 ✓	26.4 ✓	1.5	0.59	0.40 ✓	0.15 ✓
1267	26.4 ✓	27.4 ✓	1.0	2.47	7.00 ✓	6.47 ✓
1268	27.4 ✓	29.1 ✓	1.7	2.76	6.90 ✓	7.20 ✓
1269	29.1 ✓	30.3 ✓	1.2	3.03	8.41 ✓	3.96 ✓
1270	30.3 ✓	32.3 ✓	2.0	0.41	1.35 ✓	1.20 ✓
	32.3 ✓	36.2 ✓	3.9	NOT ASSAYED		
1271	36.2 ✓	37.3 ✓	1.1	0.53	1.53 ✓	1.68 ✓
1272	37.3 ✓	38.9 ✓	1.6	3.44 ✓	8.36 ✓	7.86 ✓
1273	38.9 ✓	40.3 ✓	1.4	2.94 ✓	6.75 ✓	7.52 ✓
1274	40.3 ✓	41.6 ✓	1.3	3.27 ✓	6.98 ✓	8.46 ✓
1275	41.6 ✓	43.2 ✓	1.6	3.18 ✓	6.90 ✓	8.82 ✓
1276	43.2 ✓	44.5 ✓	1.3	1.29	2.60 ✓	1.88 ✓
1277	44.5 ✓	45.1 ✓	0.6	3.06 ✓	8.88 ✓	8.77 ✓
	45.1 ✓	51.8 ✓	6.7	0.00	0.00	0.00

End of hole

LATITUDE 10684.8
 DEPARTURE 7602.59
 ELEVATION 1157.71

DIP AT COLLAR 59°
 BEARING 233° 06' 21"
 DEPTH 51.8 m (169.95 ft)

19.5m - 30.3m = 10.8m (35.4 ft)

Ag 2.01 ops.
 Pb 4.80%
 Zn 3.95%

19.5m - 32.3m = 12.8m (42.0 ft)

Ag 1.76 ops.
 Pb 4.23%
 Zn 3.52%

19.5m - 45.1m = 25.6m (84.0 ft)

36.2m - 45.1m = 8.9m (29.2 ft)

Ag 2.55 ops.
 Pb 6.03%
 Zn 6.58%

Ag 1.77 ops.
 Pb 4.23%
 Zn 4.05%

18.1.76 - 16.1.76

ASSAY NUMBER	SECTION	COKE	LENGTH (M)	Ag. wt	Pb. wt	Ag. wt	ASSAYS
1978	19.8	19.8	1.5	1.53	3.35	1.82	
1979	21.3	22.9	1.6	1.15	2.55	0.53	
1980	22.9	24.4	1.5	2.24	5.35	3.00	
1981	24.4	25.9	1.5	1.41	1.85	1.53	
1982	25.9	27.4	1.5	2.41	6.07	5.53	
1983	27.4	29.1	1.7	3.15	8.57	5.67	
1984	29.1	30.5	1.4	1.32	3.40	3.25	
1985	67.0	68.6	1.6	2.03	4.13	5.30	
1986	68.6	70.1	1.5	4.03	7.28	9.22	
1987	70.1	71.3	1.2	3.22	7.59	11.81	
1028	65.5	67.0	1.5	0.61	1.15	1.20	
1285	67.0	68.6	1.6	2.03	4.13	5.30	
1286	68.6	70.1	1.5	4.03	7.28	9.22	
1287	70.1	71.3	1.2	3.22	7.59	11.81	
1029	106.7	108.2	1.5	0.35	0.78	1.48	
1288	108.2	109.7	1.5	2.65	5.65	7.05	
1289	109.7	111.3	1.6	3.65	7.50	8.81	
1290	111.3	112.8	1.5	3.74	8.01	12.77	
1291	112.8	113.9	1.1	0.68	0.98	1.48	
1292	113.9	115.0	1.1	2.18	4.90	7.25	
1293	115.0	116.1	1.1	1.44	3.23	3.60	
1294	116.1	117.3	1.2	1.32	2.28	2.90	
1295	117.3	118.5	1.2	0.62	0.95	1.38	
1296	118.5	119.9	1.4	1.73	3.85	8.16	
1297	119.9	121.3	1.4	1.91	4.10	4.10	
1298	121.3	122.5	1.2	0.44	0.45	0.83	
1299	122.5	124.8	1.4	1.00	2.25	1.56	
1300	124.8	125.5	0.7	1.85	4.55	10.04	
1301	125.5	127.6	1.1	0.94	1.73	2.88	
1302	127.6	127.6	1.0	0.74	1.48	4.80	

127.6 ~~171.8~~ 44.2 NO. 1 ASSAYED

CONTINUED ON PAGES 32 & 33.

~~127.6~~

LATITUDE 10704.13

DIP AT CORNER -60° TOT
1159.6m

DEPARTURE 7531.34

BEARING 44°

TOT 1159.6m

ELEVATION 1166.2m

DEPTH 185.9m (607 ft)

$19.8 - 30.5m = 10.7m (35.1 ft)$

Ag 1.91 ops

Pb 4.52%

Zn 3.07%

$65.5 - 71.3 = 5.8m (19.0 ft)$

$67.0 - 71.3 = 4.3m (14.1 ft)$

Ag 3.23 ops

Pb 6.19%

Zn 8.48%

Ag 2.55 ops

Pb 4.90%

Zn 6.60%

$106.7 - 127.6 = 20.9m (68.6 ft)$

$108.2 - 127.6 = 19.4m (63.65 ft)$

Ag 1.68 ops

Pb 3.49%

Zn 5.00%

Ag 1.58 ops

Pb 3.3%

Zn 4.74%

CONTINUED ON PAGES 32 & 33

E.C.J.

ASSAY NUMBER	SECTION		CORE LENGTH (M)	ASSAYS		
	FROM	TO		Ag μ g/g	Pb %	Zn %
1303	171.8	172.9	1.1	0.88	2.15	2.00
1304	172.9	174.5	1.6	1.21	3.95	3.40
1305	174.5	175.7	1.2	1.24	4.30	4.00
1306	175.7	177.3	1.6	1.44	3.30	3.15
1307	177.3	178.6	1.3	0.97	2.40	2.25
1308	178.6	179.5	0.9	1.06	2.95	3.43
1309	179.5	181.0	1.5	1.00	2.85	2.70
1310	181.0	182.4	1.4	1.24	3.60	2.78
1311	182.4	183.8	1.4	0.68	1.60	1.28
1312	183.8	184.8	1.0	0.44	0.50	0.70
1313	184.8	185.9	1.1	0.97	2.55	2.03

End of hole.

$172.9 - 171.3 = 1.6 \text{ m (5.25 ft)}$

Ag - 1.30 μ g/g Pb 3.81 %
Zn 3.47 %

$171.8 - 185.9 = 14.1 \text{ m (46.25 ft)}$

Ag 1.04 μ g/g
Pb 2.82 %
Zn 2.56 %

LOW

(E.C.I.)

16.1.76 - 21.1.76

ASSAY NUMBER	SECTION		CORE LENGTH	ASSAYS		
	FROM	TO		Ag ops	Pb%	Zn%
	0.0 ✓	59.9 ✓	59.9	0.00	0.00	0.00
1630	59.9 ✓	60.3 ✓	0.4	4.07 ✓	9.30 ✓	18.66 ✓
1631	60.3 ✓	61.1 ✓	0.8	0.55	0.75 ✓	1.05 ✓
1314	61.1 ✓	63.0 ✓	1.9	3.41 ✓	7.69 ✓	12.72 ✓
1315	63.0 ✓	64.3 ✓	1.3	3.21 ✓	6.10 ✓	12.87 ✓
1316	64.3 ✓	65.8 ✓	1.5	1.06	2.03 ✓	8.23 ✓
1317	65.8 ✓	67.1 ✓	1.3	1.32	3.40 ✓	6.38 ✓
	67.1 ✓	106.7 ✓	39.6	0.00	0.00	0.00

End of hole

LATITUDE 10727.9
 DEPARTURE 7639.76
 ELEVATION 1151.797.

DIP AT COLLAR -36°
 BEARING 45° 58' 30"
 DEPTH 106.7 m (350 ft)

59.9 - 67.1 = 7.2 m (23.6 ft)

Ag 2.23 ops.

Pb 4.77%

Zn 9.70%

21.1.76 - 22.1.76

ASSAY NUMBER	SECTION		CORE LENGTH (M)	ASSAYS		
	From	To		Ag ogs	Pb %	Zn %
	0.0	35.7	35.7	0.00	0.00	0.00
1321	35.7	36.6	0.9	0.68	1.28	2.00
1322	36.6	38.6	2.0	1.73	3.18	5.70
1323	38.6	41.6	3.0	1.88	4.40	6.38
1324	41.6	42.4	0.8	3.38	6.81	13.53
1325	42.4	43.2	0.8	1.18	3.05	4.20
1326	43.2	45.2	2.0	2.00	3.90	7.63
1327	45.2	47.2	2.0	2.09	4.15	7.65
1328	47.2	49.2	2.0	2.38	4.75	7.65
1329	49.2	50.9	1.7	3.82	8.22	15.35
1330	50.9	52.9	2.0	0.88	1.20	1.75
1331	52.9	54.9	2.0	1.68	3.95	5.35
1332	54.9	56.2	1.3	0.53	0.43	0.55
	56.2	114.0	57.8	NOT ASSAYED		
1333	114.0	116.1	2.1	1.12	2.00	2.28
	116.1	117.7	1.6	NOT ASSAYED		
1334	117.7	120.0	2.3	1.76	4.10	7.86
	120.0	125.0	5.0	0.00	0.00	0.00

End of hole.

LATITUDE 10721.27
 DEPARTURE 7639.6
 ELEVATION 1151.797

DIP AT COLLAR -60°
 BEARING 43° 48'
 LENGTH 125 m (410 ft)

139113m

36.6 - 54.9 = 18.3m (60 ft)

Ag 2.04 ogs
 Pb 4.23 %
 Zn 7.15 %

35.7 - 56.2 = 20.5m (67.2 ft)

Ag 1.88 ogs
 Pb 3.86 %
 Zn 6.50 %

114.0 - 120.0 = 6.0m (19.7 ft)

Ag 1.07 ogs
 Pb 2.27 %
 Zn 3.81 %

117.7 - 120.0 = 2.3m (7.55 ft)

Ag 1.76 ogs Pb 4.10 % Zn 7.86 %

E.C.J.

22.1.76 - 23.1.76

ASSAY NUMBER	SECTION		CORE LENGTH (M)	ASSAYS			LATITUDE	DEPTH
	FROM	TO		Ag %	Pb %	Zn %		
	0.0 ✓	14.4 ✓	14.4	0.00	0.00	8.00		
1335	14.4 ✓	16.3 ✓	1.9	4.26 ✓	8.92 ✓	15.05 ✓		
1336	16.3 ✓	17.9 ✓	1.6	4.00 ✓	10.48 ✓	12.08 ✓		
1337	17.9 ✓	19.4 ✓	1.7	4.03 ✓	11.75 ✓	14.37 ✓		
1338	19.6 ✓	21.3 ✓	1.7	2.91 ✓	6.51 ✓	12.75 ✓		
1339	21.3 ✓	22.9 ✓	1.6	2.56	6.46 ✓	12.84 ✓		14.4
1340	22.9 ✓	24.4 ✓	1.5	2.09	4.15 ✓	8.99 ✓		
1341	24.4 ✓	25.9 ✓	1.5	2.44	5.00 ✓	8.13 ✓		
1342	25.9 ✓	27.4 ✓	1.5	1.65	2.83 ✓	3.95 ✓		
1343	27.4 ✓	29.0 ✓	1.6	0.74	1.30 ✓	1.65 ✓		
1344	29.0 ✓	30.5 ✓	1.5	2.06	4.35 ✓	9.65 ✓		
1345	30.5 ✓	32.0 ✓	1.5	2.15	6.53 ✓	11.83 ✓		
1346	32.0 ✓	33.5 ✓	1.5	3.44	9.50 ✓	17.93 ✓		
1347	33.5 ✓	35.1 ✓	1.6	2.09	4.40 ✓	10.72 ✓		
1348	35.1 ✓	36.6 ✓	1.5	1.85	3.23 ✓	5.99 ✓		
1349	36.6 ✓	38.6 ✓	2.0	2.27	4.70 ✓	7.97 ✓		
	38.6 ✓	51.9 ✓	13.3	NOT ASSAYED				
1350	51.9 ✓	53.3 ✓	1.4	6.42 ✓	2.58 ✓	4.40 ✓		
	53.3 ✓	57.6 ✓	4.3	NOT ASSAYED				
1632	57.6 ✓	58.1 ✓	0.5	0.35	0.73 ✓	0.75 ✓		
1351	58.1 ✓	59.5 ✓	1.4	1.29	2.38 ✓	4.90 ✓		
1352	59.5 ✓	61.0 ✓	1.5	1.29	2.53 ✓	4.20 ✓		
1353	61.0 ✓	62.5 ✓	1.5	0.91	2.08 ✓	3.78 ✓		
1354	62.5 ✓	64.4 ✓	1.9	1.59	1.90 ✓	4.35 ✓		
1355	64.4 ✓	65.5 ✓	1.1	1.24	1.93 ✓	3.48 ✓		5
1356	65.5 ✓	67.1 ✓	1.6	2.44	4.93 ✓	10.05 ✓		
1357	67.1 ✓	68.6 ✓	1.5	2.44	4.15 ✓	8.50 ✓		
1358	68.6 ✓	70.1 ✓	1.5	1.73	3.45 ✓	8.27 ✓		
1359	70.1 ✓	71.6 ✓	1.5	1.79	3.50 ✓	8.07 ✓		
1360	71.6 ✓	73.9 ✓	2.3	1.62	3.20 ✓	4.85 ✓		
1361	73.9 ✓	75.1 ✓	1.2	2.65	6.00 ✓	9.24 ✓		
1362	75.1 ✓	76.3 ✓	1.2	1.24	2.45 ✓	3.75 ✓		
1363	76.3 ✓	77.7 ✓	1.2	1.88	3.38 ✓	5.10 ✓		
1364	77.7 ✓	79.9 ✓	2.4	1.79	3.58 ✓	5.40 ✓		
1633	79.9 ✓	84.4 ✓	4.5	1.44	3.30 ✓	4.00 ✓		
	84.4 ✓	88.4 ✓	4.0	0.00	0.00	0.00		

End of hole.

LATITUDE 10686

DIP AT COLLAR -46°

DEPARTURE 7600.5

BEARING 44°

ELEVATION 1153 m

DEPTH 88.4 m (290 ft)

$$14.4 - 38.6 = 24.2 \text{ m (79.4 ft)}$$

Ag 2.608%

Pb 6.08%

Zn 10.32%

$$51.9 - 53.3 = 1.4 \text{ m (4.6 ft)}$$

Ag 6.42%

Pb 2.58%

Zn 4.40%

$$58.1 - 84.4 = 22.3 \text{ m (73.16 ft)}$$

Ag 1.69%

Pb 3.24%

Zn 5.64%

(E.C.J.)

24.1.76 - 25.1.76.

ASSAY NUMBER	SECTION		CORE LENGTH	ASSAYS		
	FROM	TO		Ag %	Pb %	Zn %
	0.0	20.3	20.3	0.00	0.00	0.00
1365	20.3	22.9	2.6	1.32	2.90	2.15
	22.9	29.3	6.4	NOT ASSAYED		
1366	29.3	30.5	1.2	1.03	2.28	2.05
1367	30.5	32.0	1.5	1.15	2.13	1.98
1368	32.0	33.5	1.5	1.73	3.85	3.10
1369	33.5	35.1	1.6	2.15	4.90	4.75
1370	35.1	36.6	1.5	2.79	6.78	6.22
1371	36.6	38.1	1.5	3.00	7.10	7.52
1372	38.1	39.6	1.5	1.91	4.80	3.55
1373	39.6	40.8	1.2	1.62	4.30	3.10
1374	40.8	42.2	1.4	3.68	8.10	7.09
1375	42.2	44.2	2.0	2.85	6.35	7.29
1376	44.2 44.2	45.7	1.5	3.03	5.85	7.29
1377	45.7	47.2	1.5	3.24	5.94	8.07
1378	47.2	50.0	2.8	2.06	4.88	3.55
	50.0	59.4	9.4	0.00	0.00	0.00

End of hole.

LATITUDE 10684.01
 DEPARTURE 7598.675
 ELEVATION 1155.27
 DIP AT COLLAR +31°
 BEARING 223° 48' 00"
 DEPTH 59.4 m

20.3 - 50.0 = 29.7m (97.44ft)
 Ag 1.75 %
 Pb 3.89 %
 Zn 3.48 %

29.3 - 50.0 = 20.7m (67.9ft)
 Ag 2.34 %
 Pb 5.21 %
 Zn 5.11 %

32.0 - 50.0 = 18.0m (59.1ft)
 Ag 2.53
 Pb 5.68
 Zn 5.57

E.C.J.

25.1.76 - 26.1.76

ASSAY NUMBER	SECTION		CORE LENGTH (M)	ASSAYS		
	FROM	TO		Ag. ops	Pb %	Zn %
	0.0	18.3	18.3	0.00	0.00	0.00
1379	18.3	19.8	1.5	3.50	6.75	9.96
1380	19.8	21.4	1.6	3.53	7.79	13.41
1381	21.4	23.0	1.6	3.79	7.96	11.72
	23.0	59.4	36.4	NOT ASSAYED		
1382	59.4	60.4	1.0	2.41	5.88	6.98
	60.4	71.3	10.9	NOT ASSAYED		
1383	71.3	72.8	1.5	2.74	6.68	7.47
	72.8	74.7	1.9	0.00	0.00	0.00

End of hole

LATITUDE 10685.03
 DEPARTURE 7599.64
 ELEVATION 1152.92

DIP AT COLLAR -80° (1613.8)
 BEARING 223° 48'
 DEPTH 74.7 m (245.1 ft)

18.3 - 23.0 = 4.7 m (15.42 ft)

Ag. 3.61 ops Pb. 7.52%
 Zn. 11.73%

59.4 - 60.4 = 1.0 m (3.3 ft)

Ag. 2.41 ops Pb. 5.88% Zn 6.98%

71.3 - 72.8 = 1.5 m (4.9 ft)

Ag 2.74 ops Pb 6.68% Zn 7.47%

E.C.J.

21.1.76 - 2.2.76

ASSAY NUMBER	SECTION		CORE LENGTH (M)	ASSAYS		
	FROM	TO		Ag ggs	Pb %	Zn %
1424	0.0	3.0	3.0	0.88	2.45	2.95
1425	3.0	6.1	3.1	1.76	5.05	5.10
1426	6.1	9.1	3.0	2.06	5.91	1.91
1427	9.1	11.8	2.7	1.35	3.45	5.92
1428	11.8	13.5	1.7	4.35	10.37	14.64
1429	13.5	14.7	1.2	1.15	2.53	4.60
1430	14.7	15.9	1.2	4.56	10.67	18.93
	15.9	39.6	23.7	NOT ASSAYED		
1431	39.6	41.1	1.5	3.30	1.85	7.25
1432	41.1	43.0	1.9	3.71	11.80	6.31
1433	43.0	45.9	2.9	0.94	2.58	1.75
	45.9	72.6	26.7	0.00	0.00	0.00

End of hole

LATITUDE 10716.85
 DEPARTURE 7628.66
 ELEVATION 1155.64

DIP AT COLLAR +55°
 BEARING 227° 01'
 LENGTH 72.6 m (250 ft)

0.0 - 15.9 = 15.9 m (52.17 ft)

Ag 2.04 %
 Pb 5.25 %
 Zn 7.88 %

39.6 - 45.9 = 6.3 m (20.67 ft)

Ag 2.34 ggs Pb 6.62 %
 Zn 4.43 %

29.1.76 - 30.1.76

ASSAY NUMBER	SECTION		CORE LENGTH (M)	ASSAYS		
	FROM	TO		Ag	Pb	Zn
	0.0 ✓	3.0 ✓	3.0	0.00 ✓	0.00 ✓	0.00 ✓
1634	3.0 ✓	4.6 ✓	1.6	0.78 ✓	1.63 ✓	2.03 ✓
	4.6 ✓	10.7 ✓	6.1	NOT ASSAYED		
1635	10.7 ✓	12.2 ✓	1.5	1.20 ✓	3.40 ✓	1.25 ✓
	12.2 ✓	21.3 ✓	9.1	NOT ASSAYED		
1636	21.3 ✓	22.2 ✓	0.9	0.78 ✓	2.20 ✓	0.93 ✓
1637	22.2 ✓	22.9 ✓	0.7	1.61 ✓	4.00 ✓	2.20 ✓
1384	22.9 ✓	24.4 ✓	1.5	2.88 ✓	8.11 ✓	9.81 ✓
1385	24.4 ✓	26.5 ✓	2.1	0.74 ✓	1.20 ✓	1.48 ✓
1386	26.5 ✓	27.5 ✓	1.0	3.41 ✓	5.15 ✓	5.97 ✓
1387	27.5 ✓	29.2 ✓	1.7	5.00 ✓	9.84 ✓	16.77 ✓
1388	29.2 ✓	30.4 ✓	1.2	1.76 ✓	5.36 ✓	9.05 ✓
1389	30.4 ✓	32.0 ✓	1.6	3.33 ✓	9.37 ✓	18.66 ✓
1390	32.0 ✓	34.5 ✓	2.5	2.56 ✓	6.91 ✓	12.10 ✓
1391	34.5 ✓	37.1 ✓	2.6	0.74 ✓	1.90 ✓	2.45 ✓
1392	37.1 ✓	39.6 ✓	2.5	2.03 ✓	4.45 ✓	9.49 ✓
1393	39.6 ✓	41.2 ✓	1.6	1.56 ✓	3.75 ✓	5.80 ✓
	41.2 ✓	63.6 ✓	22.4	NOT ASSAYED		
1394	63.6 ✓	65.3 ✓	1.7	3.77 ✓	9.10 ✓	7.32 ✓
1395	65.3 ✓	66.9 ✓	1.6	2.65 ✓	5.92 ✓	9.00 ✓
1396	66.9 ✓	68.6 ✓	1.7	2.80 ✓	4.95 ✓	8.85 ✓
1397	68.6 ✓	70.1 ✓	1.5	2.00 ✓	4.85 ✓	5.55 ✓
1398	70.1 ✓	72.3 ✓	2.2	2.85 ✓	7.44 ✓	8.29 ✓
1399	72.3 ✓	73.9 ✓	1.6	1.03 ✓	2.33 ✓	3.18 ✓
1400	73.9 ✓	75.5 ✓	1.6	2.47 ✓	5.31 ✓	2.38 ✓
1401	75.5 ✓	77.3 ✓	1.8	2.09 ✓	5.31 ✓	7.07 ✓
1402	77.3 ✓	79.2 ✓	1.9	2.35 ✓	5.10 ✓	4.60 ✓
1403	79.2 ✓	80.8 ✓	1.6	2.53 ✓	5.71 ✓	4.25 ✓
1404	80.8 ✓	82.3 ✓	1.5	1.41 ✓	2.95 ✓	0.90 ✓
1405	82.3 ✓	83.8 ✓	1.5	2.82 ✓	6.37 ✓	4.80 ✓
1406	83.8 ✓	85.6 ✓	1.8	1.62 ✓	3.88 ✓	4.05 ✓
	85.6 ✓	99.1 ✓	13.5	0.00 ✓	0.00 ✓	0.00 ✓

End of hole

LATITUDE 10,720.18

DIP AT CORNER -47°

DEPARTURE 7631.99

BEARING 227°

ELEVATION 1151.71

LENGTH 99.1 m (325 ft)

 $22.2 - 41.2 = 19.0 \text{ m. (62.34 ft)}$

Ag 2.23%

Pb 5.27%

Zn 8.64%

 $63.6 - 85.6 = 22.0 \text{ m. (72.18 ft)}$

Ag 2.29%

Pb 5.34%

Zn 5.50%

31.1.76 - 31.1.76.

ASSAY NUMBER	SECTION		CORE LENGTH (M)	ASSAYS		
	FROM	TO		Ag ops	Pb %	Zn %
1638	0.0 ✓	1.9 ✓	1.9 ✓	0.48	2.03 ✓	2.55 ✓
	1.9 ✓	8.8 ✓	6.9	NOT	ASSAYED	
1639	8.8 ✓	11.7 ✓	2.9	0.55	1.42 ✓	2.55 ✓
	11.7 ✓	19.3 ✓	7.6	NOT	ASSAYED	
1640	19.3 ✓	22.3 ✓	3.0	0.48	1.18 ✓	3.50 ✓
1641	22.3 ✓	23.9 ✓	1.6	0.48	1.94 ✓	2.50 ✓
	23.9 ✓	31.8 ✓	7.9	NOT	ASSAYED	
1407	31.8 ✓	33.5 ✓	1.7	2.09	4.90 ✓	5.90 ✓
1408	33.5 ✓	35.1 ✓	1.6	1.76	3.73 ✓	5.92 ✓
1409	35.1 ✓	36.6 ✓	1.5	2.18	4.30 ✓	7.65 ✓
1410	36.6 ✓	38.1 ✓	1.5	2.85	5.60 ✓	10.01 ✓
1411	38.1 ✓	39.6 ✓	1.5	2.59	5.20 ✓	9.18 ✓
1412	39.6 ✓	41.1 ✓	1.5	0.71	1.40 ✓	3.20 ✓
1413	41.1 ✓	42.7 ✓	1.6	1.32	3.10 ✓	6.15 ✓
1414	42.7 ✓	44.2 ✓	1.5	2.38	4.33 ✓	7.47 ✓
1415	44.2 ✓	45.7 ✓	1.5	1.29	2.73 ✓	3.48 ✓
1416	45.7 ✓	47.2 ✓	1.5	2.31	4.15 ✓	8.54 ✓
1417	47.2 ✓	48.8 ✓	1.6	1.32	2.23 ✓	2.28 ✓
1418	48.8 ✓	51.2 ✓	2.4	1.50	2.75 ✓	3.70 ✓
1419	51.2 ✓	52.9 ✓	1.7	0.38	0.40 ✓	0.55 ✓
1420	52.9 ✓	54.9 ✓	2.0	0.83	1.43 ✓	1.63 ✓
1421	54.9 ✓	56.7 ✓	1.8	1.29	2.78 ✓	3.58 ✓
1422	56.7 ✓	57.9 ✓	1.2	1.35	2.73 ✓	4.55 ✓
	57.9 ✓	67.1 ✓	9.2	NOT	ASSAYED	
1642	67.1 ✓	67.8 ✓	0.7	0.52	0.48 ✓	0.93 ✓
1423	67.8 ✓	70.1 ✓	2.3	1.94	4.00 ✓	7.55 ✓

End of hole

LATITUDE 10720.8

DIP AT COLLAR. -68°

DEPARTURE 7632.835

BEARING 47°

ELEVATION 1151.74

LENGTH 70.1 m (230 ft).

$$31.8 - 57.9 = 26.1 \text{ m (85.6 ft)}$$

Ag 1.61

Pb 3.17

Zn 5.07.

$$67.8 - 70.1 = 2.3 \text{ m (7.55 ft)}$$

Ag 1.940% Pb 4.00% Zn 7.55%

U-24

No ✓

RECORDS

E.C.J.

Reported on
Re drilled by
U-25

DDH U. 24

LAT 10720.67. DEP 7640.42

DIP $+34\frac{1}{2}^{\circ}$ BEARING $47^{\circ} 24'$

ELEVATION 1155.16. LENGTH 59.4m

NO ASSAYS

E.C.J.

5.2.76 - 7.2.76

ASSAY NUMBER	SECTION		CORE LENGTH (M)	ASSAYS		
	FROM (M)	TO (M)		Ag. ogs.	Pb%	Zn%
	0.0 ✓	59.5 ✓	59.5	0.00 ✓	0.00 ✓	0.00 ✓
1443	59.5 ✓	61.0 ✓	1.5	1.36 ✓	2.18 ✓	3.10 ✓
1444	61.0 ✓	62.5 ✓	1.5	0.45 ✓	0.88 ✓	2.85 ✓
1434	62.5 ✓	65.5 ✓	3.0	1.91 ✓	3.35 ✓	11.52 ✓
1435	65.5 ✓	68.6 ✓	3.1	1.00 ✓	1.70 ✓	3.25 ✓
1436	68.6 ✓	72.3 ✓	3.7	1.03 ✓	1.63 ✓	4.03 ✓
	72.3 ✓	90.7 ✓	18.4	NOT ASSAYED		
1437	90.7 ✓	93.0 ✓	2.3	0.85 ✓	1.78 ✓	3.43 ✓
1438	93.0 ✓	95.8 ✓	2.8	0.88 ✓	1.83 ✓	3.85 ✓
1439	95.8 ✓	97.5 ✓	1.7	1.15 ✓	2.58 ✓	5.28 ✓
1440	97.5 ✓	99.5 ✓	2.0	1.15 ✓	2.35 ✓	3.58 ✓
1441	99.5 ✓	101.9 ✓	2.4	3.53 ✓	8.18 ✓	15.27 ✓
	101.9 ✓	114.3 ✓	12.4	0.00 ✓	0.00 ✓	0.00 ✓

End of hole

LATITUDE
 DEPARTURE
 ELEVATION

DIP AT COLLAR.
 BEARING
 DEPTH: 114.3m (375 ft)

62.5 - 72.3 = 9.8m (32.15 ft)
 Ag. 1.29 ogs
 Pb 2.18%
 Zn 6.04%

90.7 - 101.9 = 11.2m (36.75 ft)
 Ag 1.53 ogs
 Pb 3.39%
 Zn 6.38%

95.8 - 101.9 = 6.1m (20.0 ft)
 Ag 2.09 ogs
 Pb 4.71%
 Zn 8.65%

8.2.76 - 9.2.76

ASSAY NUMBER	SECTION		CORE LENGTH (M)	ASSAYS		
	FROM (M)	TO (M)		Ag μ g	Pb %	Zn %
1442	0.0 ✓	1.5 ✓	1.5	0.80	1.25 ✓	0.48 ✓
1443	1.5 ✓	3.0 ✓	1.5	0.24	0.25 ✓	2.20 ✓
1444	3.0 ✓	4.6 ✓	1.6	0.91	1.75 ✓	4.40 ✓
1445	4.6 ✓	6.1 ✓	1.5	2.44	4.70 ✓	11.21 ✓
1446	6.1 ✓	7.6 ✓	1.5	0.97	2.00 ✓	3.43 ✓
1447	7.6 ✓	9.1 ✓	1.5	0.68	1.42 ✓	2.73 ✓
1448	9.1 ✓	10.7 ✓	1.6	0.80	1.67 ✓	4.20 ✓
1449	10.7 ✓	12.2 ✓	1.5	1.41	2.90 ✓	7.69 ✓
1450	12.2 ✓	13.7 ✓	1.5	1.65	3.65 ✓	7.61 ✓
1451	13.7 ✓	15.2 ✓	1.5	1.38	2.80 ✓	7.79 ✓
1452	15.2 ✓	16.8 ✓	1.6	1.79	4.08 ✓	7.81 ✓
1453	16.8 ✓	18.3 ✓	1.5	0.68	1.65 ✓	4.75 ✓
1454	18.3 ✓	19.8 ✓	1.5	1.21	3.10 ✓	6.01 ✓
1455	19.8 ✓	21.3 ✓	1.5	1.32	2.90 ✓	6.42 ✓
1456	21.3 ✓	22.9 ✓	1.6	1.47	3.10 ✓	5.71 ✓
1457	22.9 ✓	24.4 ✓	1.5	0.84	1.35 ✓	3.80 ✓
1458	24.4 ✓	25.9 ✓	1.5	0.42	0.98 ✓	3.05 ✓
1459	25.9 ✓	27.4 ✓	1.5	0.32	0.85 ✓	1.18 ✓
1460	27.4 ✓	29.0 ✓	1.6	1.26	2.60 ✓	2.33 ✓
1461	29.0 ✓	30.5 ✓	1.5	0.97	1.78 ✓	3.53 ✓
1462	30.5 ✓	32.0 ✓	1.5	1.26	1.88 ✓	4.13 ✓
1463	32.0 ✓	33.5 ✓	1.5	1.13	1.88 ✓	3.55 ✓
1464	33.5 ✓	35.1 ✓	1.6	0.88	2.05 ✓	1.88 ✓
1465	35.1 ✓	36.6 ✓	1.5	0.52	1.17 ✓	1.85 ✓
1466	36.6 ✓	38.6 ✓	2.0	0.26	0.68 ✓	1.63 ✓
1467	38.6 ✓	40.0 ✓	1.4	3.49	4.20 ✓	5.53 ✓
	40.0 ✓	48.1 ✓	8.1	NOT	ASSAYED	
1468	48.1 ✓	50.3 ✓	2.2	1.61	3.25 ✓	8.20 ✓
1469	50.3 ✓	52.4 ✓	2.1	1.68	2.90 ✓	7.64 ✓
1470	52.4 ✓	55.1 ✓	2.7	2.10	4.70 ✓	8.12 ✓
1471	55.1 ✓	56.4 ✓	1.3	0.93	1.73 ✓	4.13 ✓
1472	56.4 ✓	59.0 ✓	2.6	0.61	1.40 ✓	2.68 ✓
	59.0 ✓	76.2 ✓	17.2	0.00	0.00	0.00

End of hole.

LATITUDE 10777.49

DIP AT COLLAR $+69^{\circ}$

DEPARTURE 7689.09

BEARING $235^{\circ} 18' 48''$

ELEVATION 1156.85

DEPTH 76.2 m (250 ft)

$$3.0 - 24.4 = 21.4 \text{ m (70.2 ft)}$$

Ag. 1.25 ggs.

Pb 2.61 g

Zn 5.96 g

$$24.4 \text{ m} - 40.0 \text{ m} = 15.6 \text{ m (51.5 ft)}$$

Ag 1.01 ggs

Pb 1.76 g

Zn 2.80 g

LOW

$$38.6 \text{ m} - 40 \text{ m} = 1.4 \text{ m (4.6 ft)} \text{ Ag. } 3.49 \text{ ggs Pb. } 4.20 \text{ g Zn } 5.53 \text{ g}$$

13.2.76 - 15.2.76

ASSAY NUMBER	SECTION		CORE LENGTH	ASSAYS		
	FROM (m)	TO (m)		GRAMS Ag/TONNE	Pb %	Zn %
1473	0.0 ✓	1.5 ✓	1.5	84.69 ✓	6.85 ✓	10.29 ✓
1474	1.5 ✓	3.0 ✓	1.5	40.46 ✓	2.83 ✓	4.50 ✓
1475	3.0 ✓	4.6 ✓	1.6	42.51 ✓	3.35 ✓	3.20 ✓
1476	4.6 ✓	6.1 ✓	1.5	50.40 ✓	3.10 ✓	1.95 ✓
1477	6.1 ✓	7.6 ✓	1.5	25.97 ✓	0.98 ✓	0.60 ✓
1478	7.6 ✓	9.1 ✓	1.5	46.29 ✓	2.25 ✓	2.90 ✓
1479	9.1 ✓	11.2 ✓	2.1	36.34 ✓	2.23 ✓	4.15 ✓
	11.2 ✓	13.6 ✓	2.4 m	NOT	ASSAYED	
1480	13.6 ✓	15.2 ✓	1.6	26.40 ✓	1.20 ✓	2.05 ✓
1481	15.2 ✓	16.8 ✓	1.6	36.34 ✓	2.88 ✓	3.10 ✓
1482	16.8 ✓	18.3 ✓	1.5	24.34 ✓	1.25 ✓	2.35 ✓
1483	18.3 ✓	19.8 ✓	1.5	48.54 ✓	3.35 ✓	3.62 ✓
1484	19.8 ✓	23.0 ✓	3.2	69.60 ✓	5.56 ✓	5.45 ✓
	23.0 ✓	24.1 ✓	1.1	NOT	ASSAYED	
1485	24.1 ✓	25.9 ✓	1.8	38.40 ✓	2.18 ✓	5.39 ✓
1486	25.9 ✓	27.4 ✓	1.5	40.46 ✓	2.43 ✓	4.30 ✓
	27.4 ✓	29.4 ✓	2.0	NOT	ASSAYED	
1487	29.4 ✓	30.5 ✓	1.1	28.46 ✓	1.55 ✓	2.70 ✓
1488	30.5 ✓	32.0 ✓	1.5	65.49 ✓	3.68 ✓	1.68 ✓
1489	32.0 ✓	33.5 ✓	1.5	29.14 ✓	1.63 ✓	3.95 ✓
1490	33.5 ✓	35.1 ✓	1.6	30.17 ✓	1.93 ✓	4.30 ✓
1491	35.1 ✓	36.6 ✓	1.5	24.34 ✓	1.25 ✓	2.10 ✓
1492	36.6 ✓	38.1 ✓	1.5	41.49 ✓	2.65 ✓	2.55 ✓
1493	38.1 ✓	39.6 ✓	1.5	45.26 ✓	2.20 ✓	5.50 ✓
1494	39.6 ✓	41.1 ✓	1.5	53.49 ✓	2.68 ✓	7.18 ✓
1495	41.1 ✓	42.7 ✓	1.6	61.51 ✓	3.90 ✓	6.16 ✓
1496	42.7 ✓	45.7 ✓	3.0	34.29 ✓	1.45 ✓	3.45 ✓
1497	45.7 ✓	48.8 ✓	3.1	32.23 ✓	1.75 ✓	3.15 ✓
1498	48.8 ✓	51.8 ✓	3.0	41.49 ✓	2.75 ✓	5.93 ✓
1499	51.8 ✓	54.9 ✓	3.1	56.57 ✓	3.45 ✓	6.92 ✓
1500	54.9 ✓	57.9 ✓	3.0	31.20 ✓	1.70 ✓	3.18 ✓
1501	57.9 ✓	61.0 ✓	3.1	30.17 ✓	1.75 ✓	2.40 ✓
1502	61.0 ✓	64.0 ✓	3.0	40.46 ✓	2.73 ✓	4.80 ✓
1503	64.0 ✓	67.1 ✓	3.1	82.63 ✓	5.90 ✓	10.84 ✓
1504	67.1 ✓	69.7 ✓	2.6	9.94 ✓	0.33 ✓	3.95 ✓
1505	69.7 ✓	71.6 ✓	1.9	117.94 ✓	8.35 ✓	13.94 ✓
1506	71.6 ✓	73.2 ✓	1.6	93.94 ✓	7.27 ✓	12.82 ✓
1507	73.2 ✓	75.4 ✓	2.2	65.49 ✓	4.00 ✓	7.89 ✓
	75.4 ✓	92.7 ✓	17.3	NOT	ASSAYED	

LATITUDE 10781.03

DIP AT CORNER + 62°

DEPARTURE 7693.72

BEARING 48° 25' 09"

ELEVATION 1157.39

DEPTH 106.1 m (348.1 ft)

0.0 m - 11.2 m = 11.2 m (36.74 ft)

Ag 47.29 gms/tonne

Pb 3.04%

Zn 3.95%

18.3 m - 23.0 m = 4.7 m (15.42 ft)

Ag 61.28 gms/tonne Pb 4.85%

Zn 4.87%

24.1 - 27.4 = 3.3 m (10.83 ft)

Ag 39.34 gms/tonne Pb 2.29%

Zn 4.89%

18.3 m - 27.4 m = 9.1 m (29.86 ft)

Ag 45.92 gms/tonne

Pb 3.34%

Zn 4.29%

29.4 m - 75.4 m = 46.0 m (151 ft)

Ag 47.36 grams/tonne

Pb 2.94%

Zn 5.68%

DDH U 27Continued on Pages 56 & 57.

E.C.I.

ASSAY NUMBER	SECTION		CORE LENGTH	ASSAYS		
	FROM (m)	TO (m)		Ag ^{GRAMMES} per tonne	Pb %	Zn %
1508	92.7	94.5	1.8	75.77	3.88	8.03
1509	94.5	96.0	1.5	33.26	2.23	3.60
1510	96.0 96.0	97.5	1.5	81.60	5.70	6.84
1511	97.5	99.1	1.6	33.26	2.05	2.95
1645	99.1	100.6	1.5	18.17	1.20	2.35
1646	100.6	102.1	1.5	34.29	2.80	3.30
1647	102.1	103.5	1.4	12.00	0.90	2.33
1648	103.5	103.9	0.4	31.20	1.93	4.35
1512	103.9	106.1	2.2	66.51	4.18	6.32

End of hole.

$$92.7\text{m} - 106.1\text{m} = 13.4\text{m} \text{ (44 ft)}$$

Ag 45.98 grams/tonne

Pb 2.94%

Zn 4.64%



16.2.76 - 17.2.76

ASSAY NUMBER	SECTION		CORE LENGTH (M)	ASSAYS		
	FROM (M)	TO (M)		Grams Ag / tonne	Pb %	Zn %
1513	0.0 ✓	7.4 ✓	7.4	0.00	0.00	0.00
	7.4 ✓	9.0 ✓	1.6	8.23	0.53	0.48
1514	9.0 ✓	10.1 ✓	1.1	15.09	0.97	0.70
1515	10.7 ✓	13.2 ✓	2.5	0.34	0.04	0.03
1516	13.2 ✓	14.8 ✓	1.6	25.37	0.68	0.20
1517	14.8 ✓	15.5 ✓	0.7	102.86	7.24	4.75
1518	15.5 ✓	17.6 ✓	2.1	95.66	7.50	5.75
1519	17.6 ✓	19.8 ✓	2.2	146.74	11.85	8.71
1520	19.8 ✓	21.3 ✓	1.5	186.52	14.95	9.52
1521	21.3 ✓	22.1 ✓	0.8	64.46	4.83	3.60
	22.1 ✓	55.3 ✓	33.2	NOT ASSAYED		
1522	55.3 ✓	56.7 ✓	1.4	4.11	0.22	0.63
1523	56.7 ✓	57.9 ✓	1.2	179.66	8.50	13.85
1524	57.9 ✓	59.4 ✓	1.5	116.92	7.53	10.08
1525	59.4 ✓	61.0 ✓	1.6	151.20	7.78	12.37
1526	61.0 ✓	62.5 ✓	1.5	109.94	6.75	12.62
1527	62.5 ✓	64.0 ✓	1.5	110.06	6.82	10.46

End of hole

LATITUDE 10408.75

DIP AT COLLAR -39° 13'

DEPARTURE 7538.75

BEARING 48° 42' 12"

ELEVATION 1166.52m

DEPTH 64 m (210 ft)

14.8 m - 22.1 m = 7.3 m (24 ft)

Ag - 127 grams/tonne

Pb 10.02 %

Zn 7.09 %

56.7 - 64.0 = 7.3 m (24 ft)

Ag 131.9 grams/tonne

Pb 7.44 %

Zn 12.18 %

17.2.76 - 18.2.76

ASSAY NUMBER	SECTION		CORE LENGTH	ASSAYS		
	FROM (m)	TO (m)		Ag / tonne	Pb %	Zn %
1528	0.0 ✓	22.6 ✓	22.6	0.00	0.00	0.00
	22.6 ✓	25.4 ✓	2.8	35.31 ✓	2.13 ✓	1.95 ✓
	25.4 ✓	54.9 ✓	29.5	NOT	ASSAYED	
1529	54.9 ✓	55.4 ✓	0.5	TR ✓	0.03 ✓	0.58 ✓
1530	55.4 ✓	55.7 ✓	0.3	40.46 ✓	4.45 ✓	7.63 ✓
1531	55.7 ✓	56.5 ✓	0.8	77.83 ✓	5.65 ✓	9.01 ✓
1532	56.5 ✓	57.7 ✓	1.2	8.91 ✓	0.50 ✓	1.23 ✓
1533	57.7 ✓	59.6 ✓	1.9	106.97 ✓	7.47 ✓	13.19 ✓
1534	59.6 ✓	60.6 ✓	1.0	90.86 ✓	6.70 ✓	15.73 ✓
1535	60.6 ✓	61.5 ✓	0.9	48.34 ✓	3.03 ✓	7.36 ✓
1536	61.5 ✓	63.7 ✓	2.2	34.29 ✓	1.88 ✓	2.85 ✓
1537	63.7 ✓	65.5 ✓	1.8	17.14 ✓	0.95 ✓	2.78 ✓
1538	65.5 ✓	68.6 ✓	3.1	30.17 ✓	1.73 ✓	3.80 ✓

End of hole

LATITUDE 10709.13
DEPARTURE 7538.50
ELEVATION 1167.26

DIP AT COLLAR -13° 51'
BEARING 46° 14' 03"
DEPTH 68.6 m (225 ft)

55.4m - 61.5m = 6.1m (20 ft)
Ag. 69.3 grams per tonne
Pb. 4.93 %
Zn 9.51 %

E.C.J.

19.2.76. 20.2.76

ASSAY NUMBER	SECTION		CORE LENGTH	ASSAYS		
	FROM (M)	TO (M)		Ag ^{grams} / tonne	Pb %	Zn %
	0.0	13.7	13.7	0.00	0.00	0.00
1554	13.7	15.2	1.5	2.06	0.23	0.18
1555	15.2	16.8	1.6	20.23	1.40	1.10
1556	16.8	17.8	1.0	13.03	0.85	0.50
1557	17.8	18.1	0.3	16.11	1.03	0.73
1558	18.1	19.8	1.7	35.31	2.83	2.05
1559	19.8	21.0	1.2	31.20	2.20	1.10
1560	21.0	22.0	1.0	17.14	1.40	1.13
1561	22.0	22.6	0.6	4.11	0.38	0.35
	22.6	27.3	4.7	NOT ASSAYED		
1562	27.3	28.5	1.2	19.20	1.43	0.93
	28.5	29.2	0.7	NOT ASSAYED		
1563	29.2	29.6	0.4	27.43	1.03	0.60
1564	29.6	30.7	1.1	103.89	8.11	5.17
1565	30.7	32.0	1.3	27.43	2.25	1.63
1566	32.0	33.5	1.5	24.84	2.05	0.83
1567	33.5	35.1	1.6	132.00	11.12	3.88
1568	35.1	35.8	0.7	55.84	3.60	1.55
1569	35.8	38.1	2.3	121.03	10.12	4.35
1570	38.1	38.9	0.8	67.54	5.71	3.95
	38.9	39.6	0.7	NOT ASSAYED		
1571	39.6	39.9	0.3	8.91	0.68	0.45
	39.9	61.0	21.1	0.00	0.00	0.00

End of hole

LATITUDE 10702.96
 DEPARTURE 7535.11
 ELEVATION 1166.86
 DIP AT COLLAR -15° 45'
 BEARING 92° 35' 49"
 DEPTH 61.0 m (200 ft)

29.6 - 38.9 = 9.3 m (30.5 ft)

Ag 82.68 grams per tonne

Pb 6.78%

Zn 3.17%

20.2.76 · 23.2.76

ASSAY NUMBER	SECTION		CORE LENGTH (M)	ASSAYS		
	FROM (M)	TO (M)		Ag ^{grams} / tonne	Pb %	Zn %
1572	0.0 ✓	1.8 ✓	1.8	38.40 ✓	2.48 ✓	4.98 ✓
	1.8 ✓	28.2 ✓	26.4	NOT ASSAYED		
1573	28.2 ✓	29.3 ✓	1.1	8.23 ✓	0.48 ✓	0.33 ✓
1574	29.3 ✓	30.5 ✓	1.2	41.49 ✓	2.43 ✓	1.90 ✓
	30.5 ✓	53.4 ✓	22.9	NOT ASSAYED		
1575	53.4 ✓	54.7 ✓	1.3	98.74 ✓	5.12 ✓	8.92 ✓
	54.7 ✓	90.1 ✓	35.4	NOT ASSAYED		
1576	90.1 ✓	92.3 ✓	2.2	49.37 ✓	3.90 ✓	4.50 ✓
1577	92.3 ✓	93.0 ✓	0.7	9.94 ✓	0.25 ✓	0.23 ✓
	93.0 ✓	107.9 ✓	14.9	NOT ASSAYED		
1578	107.9 ✓	109.7 ✓	1.8	25.37 ✓	1.90 ✓	1.90 ✓
1579	109.7 ✓	111.3 ✓	1.6	17.14 ✓	1.30 ✓	0.88 ✓
1580	111.3 ✓	113.0 ✓	1.7	9.94 ✓	0.50 ✓	0.95 ✓
	113.0 ✓	121.9 ✓	8.9	0.00 ✓	0.00 ✓	0.00 ✓

End of hole

LATITUDE 10703.10

DIP AT CORNER -72° 51'

DEPARTURE 1592.66

BEARING 222° 33' 27"

ELEVATION 1166.37

DEPTH 121.9 m (400 ft)

0.0-1.8 = 1.8 m (5.9 ft) Ag. 38.4 gms. ton Pb 2.48% Zn 4.98%

53.4-54.7 = 1.3 m (4.27 ft) Ag 98.74 gms. ton Pb 5.12% Zn 8.92%

90.1-92.3 = 2.2 m (7.22 ft) Ag 49.37 gms. ton Pb 3.90% Zn 4.50%

23.2.76 - 24.2.76

ASSAY NUMBER	SECTION		CORE LENGTH (M)	ASSAYS		
	FROM (M)	TO (M)		Ag. ^{grams} / ton	Pb %	Zn %
	0.0 ✓	2.8 ✓	2.8	0.00	0.00	0.00
1581	2.8 ✓	3.4 ✓	0.6	71.66 ✓	4.43 ✓	3.25 ✓
1582	3.4 ✓	5.1 ✓	1.7	19.20 ✓	1.10 ✓	1.13 ✓
	5.1 ✓	6.2 ✓	1.1	NOT ASSAYED		
1583	6.2 ✓	7.8 ✓	1.6	88.8 ✓	6.05 ✓	1.93 ✓
	7.8 ✓	21.9 ✓	14.1	0.00	0.00	0.00

End of hole.

LATITUDE 10700.57
 DEPARTURE 7330.24
 ELEVATION 1169.11

DIP AT COLLAR -45°
 BEARING 224°
 DEPTH 21.9 m (72 ft)

2.8 - 1.8 = 5.0 m (16.4 ft)
 Ag 43.54 gms. / ton
 Pb 2.84 %
 Zn 3.31 %

LOW

24.2.76 - 28.2.76

ASSAY NUMBER	SECTION		CORE LENGTH (M)	ASSAYS		
	FROM (M)	TO (M)		grams Ag. Tonne	Pb %	Zn %
1584	0.0 ✓	1.9 ✓	1.9	35.31 ✓	2.88 ✓	3.65 ✓
1585	1.9 ✓	4.4 ✓	2.5	8.23 ✓	0.72 ✓	0.13 ✓
1586	4.4 ✓	6.1 ✓	1.7	15.09 ✓	1.53 ✓	1.50 ✓
1587	6.1 ✓	8.3 ✓	2.2	32.23 ✓	2.20 ✓	4.08 ✓
	8.3 ✓	46.7 ✓	38.4	NOT ASSAYED		
1588	46.7 ✓	48.4 ✓	1.7	15.09 ✓	0.63 ✓	0.93 ✓
1589	48.4 ✓	50.3 ✓	1.9	140.23 ✓	7.51 ✓	12.47 ✓
1590	50.3 ✓	51.8 ✓	1.5	44.23 ✓	2.95 ✓	3.73 ✓
1591	51.8 ✓	53.3 ✓	1.5	120.00 ✓	5.63 ✓	8.08 ✓
1592	53.3 ✓	54.9 ✓	1.6	71.66 ✓	4.13 ✓	6.84 ✓
1593	54.9 ✓	56.4 ✓	1.5	50.40 ✓	3.40 ✓	6.24 ✓
1594	56.4 ✓	57.9 ✓	1.5	42.51 ✓	2.65 ✓	6.23 ✓
1595	57.9 ✓	59.4 ✓	1.5	69.60 ✓	4.10 ✓	8.08 ✓
1596	59.4 ✓	61.0 ✓	1.6	57.60 ✓	3.40 ✓	5.14 ✓
1597	61.0 ✓	62.5 ✓	1.5	73.71 ✓	3.63 ✓	5.69 ✓
1598	62.5 ✓	64.0 ✓	1.5	114.17 ✓	6.22 ✓	9.60 ✓
1599	64.0 ✓	65.5 ✓	1.5	105.94 ✓	5.40 ✓	9.15 ✓
1600	65.5 ✓	67.1 ✓	1.6	38.40 ✓	2.73 ✓	6.41 ✓
1701	67.1 ✓	68.6 ✓	1.5	100.80 ✓	5.62 ✓	9.50 ✓
1702	68.6 ✓	70.1 ✓	1.5	44.23 ✓	3.13 ✓	6.01 ✓
1703	70.1 ✓	71.6 ✓	1.5	73.71 ✓	4.55 ✓	7.88 ✓
1704	71.6 ✓	73.2 ✓	1.6	57.60 ✓	3.23 ✓	5.06 ✓
1705	73.2 ✓	74.7 ✓	1.5	44.23 ✓	2.60 ✓	5.37 ✓
1706	74.7 ✓	76.2 ✓	1.5	60.34 ✓	3.45 ✓	6.67 ✓
1707	76.2 ✓	77.7 ✓	1.5	41.49 ✓	3.00 ✓	4.90 ✓
1708	77.7 ✓	79.2 ✓	1.5	52.46 ✓	4.00 ✓	4.23 ✓
1709	79.2 ✓	80.8 ✓	1.6	59.31 ✓	3.65 ✓	6.41 ✓
1710	80.8 ✓	82.3 ✓	1.5	62.40 ✓	4.27 ✓	7.35 ✓
1711	82.3 ✓	83.8 ✓	1.5	70.63 ✓	5.51 ✓	1.98 ✓
1712	83.8 ✓	85.3 ✓	1.5	71.66 ✓	4.58 ✓	7.25 ✓
1713	85.3 ✓	86.9 ✓	1.6	50.40 ✓	3.25 ✓	5.47 ✓
1714	86.9 ✓	88.4 ✓	1.5	57.60 ✓	4.50 ✓	6.28 ✓
1715	88.4 ✓	89.9 ✓	1.5	100.80 ✓	6.79 ✓	11.13 ✓
1716	89.9 ✓	91.4 ✓	1.5	60.34 ✓	3.98 ✓	3.78 ✓
1717	91.4 ✓	93.0 ✓	1.6	63.43 ✓	4.48 ✓	7.83 ✓
1718	93.0 ✓	94.5 ✓	1.5	63.43 ✓	4.46 ✓	6.81 ✓
1719	94.5 ✓	96.0 ✓	1.5	55.54 ✓	4.36 ✓	8.85 ✓
1720	96.0 ✓	97.5 ✓	1.5	80.57 ✓	6.36 ✓	8.08 ✓
1721	97.5 ✓	99.1 ✓	1.6	55.54 ✓	4.81 ✓	6.02 ✓

LATITUDE 3N

DIP AT COLLAR -90°

DEPARTURE 74W

BEARING.

ELEVATION.

DEPTH 126.5 m. (415 ft)

6.1 m - 8.3 m = 2.2 m (7.2 ft) Ag. 32.23 gms. Tonne. Pb 2.20% Zn 4.08% **LOW**

48.4 - 99.1 = 50.7 m (166.34 ft)

Ag 66.84 gms. Tonne

Pb 4.4%

Zn 7.01%

TDH u 34 continued on

PAGES 72 - 73 -

EOL

ASSAY NUMBER	SECTION		CORE LENGTH (M)	ASSAYS		
	FROM (M)	TO (M)		Ag ^{grams.} ounce	Pb %	Zn %
1722	99.1 ✓	100.6 ✓	1.5	6.17 ✓	0.05 ✓	0.35 ✓
1723	100.6 ✓	102.1 ✓	1.5	17.14 ✓	0.25 ✓	1.75 ✓
1724	102.1 ✓	103.6 ✓	1.5	8.23 ✓	0.10 ✓	1.53 ✓
1725	103.6 ✓	105.2 ✓	1.6	8.91 ✓	0.15 ✓	0.33 ✓
1726	105.2 ✓	106.7 ✓	1.5	25.37 ✓	1.30 ✓	1.10 ✓
1727	106.7 ✓	108.1 ✓	1.4	33.26 ✓	2.00 ✓	1.45 ✓
	108.1 ✓	126.5 ✓	18.4	0.00 ✓	0.00 ✓	0.00 ✓

End of hole

E.C.I.

ASSAY NUMBER	SECTION		CORE LENGTH (M)	ASSAYS		
	FROM (M)	TO (M)		Ag ^{grams} / _{tonne}	Pb %	Zn %
1728	0.0 ✓	1.5 ✓	1.5	30.17 ✓	1.89 ✓	3.70 ✓
1729	1.5 ✓	4.4 ✓	2.9	16.11 ✓	1.04 ✓	2.28 ✓
1730	4.4 ✓	6.7 ✓	2.3	34.29 ✓	2.10 ✓	4.20 ✓
1731	6.7 ✓	8.0 ✓	1.3	10.97 ✓	0.58 ✓	1.00 ✓
	8.0 ✓	51.0 ✓	43.0	NOT ASSAYED		
1732	51.0 ✓	52.1 ✓	1.1	41.49 ✓	2.58 ✓	5.87 ✓
	52.1 ✓	59.4 ✓	7.3	NOT ASSAYED		
1733	59.4 ✓	61.5 ✓	2.1	25.37 ✓	1.05 ✓	2.00 ✓
1734	61.5 ✓	62.5 ✓	1.0	66.51 ✓	3.75 ✓	5.00 ✓
1735	62.5 ✓	64.0 ✓	1.5	54.51 ✓	2.93 ✓	4.55 ✓
1736	64.0 ✓	65.5 ✓	1.5	68.57 ✓	3.95 ✓	6.48 ✓
1737	65.5 ✓	67.1 ✓	1.6	55.54 ✓	3.45 ✓	5.49 ✓
1738	67.1 ✓	68.6 ✓	1.5	53.49 ✓	4.03 ✓	5.59 ✓
1739	68.6 ✓	70.1 ✓	1.5	101.83 ✓	5.80 ✓	7.35 ✓
1740	70.1 ✓	71.6 ✓	1.5	41.49 ✓	2.83 ✓	1.98 ✓
1741	71.6 ✓	73.2 ✓	1.6	81.60 ✓	6.30 ✓	9.47 ✓
1742	73.2 ✓	74.7 ✓	1.5	100.80 ✓	6.60 ✓	9.95 ✓
1743	74.7 ✓	76.2 ✓	1.5	110.06 ✓	6.50 ✓	11.90 ✓
1744	76.2 ✓	77.7 ✓	1.5	125.14 ✓	6.36 ✓	11.64 ✓
1745	77.7 ✓	79.2 ✓	1.5	29.14 ✓	1.70 ✓	2.33 ✓
1746	79.2 ✓	81.1 ✓	1.9	12.69 ✓	4.25 ✓	9.44 ✓
	81.1 ✓	85.3 ✓	4.2	NOT ASSAYED		
1747	85.3 ✓	86.9 ✓	1.6	30.17 ✓	2.60 ✓	3.10 ✓
1748	86.9 ✓	88.4 ✓	1.5	33.26 ✓	2.80 ✓	2.75 ✓
1749	88.4 ✓	90.5 ✓	2.1	14.06 ✓	0.94 ✓	1.65 ✓
	90.5 ✓	106.7 ✓	16.2	NOT ASSAYED		
1750	106.7 ✓	108.2 ✓	1.5	15.09 ✓	1.10 ✓	1.93 ✓
	108.2 ✓	147.8 ✓	39.6	0.00 ✓	0.00 ✓	0.00 ✓

End of hole

LATITUDE 3N
DEPARTURE 74N
ELEVATION

DIP AT COLLAR
BEARING
DEPTH 147.8 m (485 ft)

4.4 - 6.7 = 2.3 m (7.55 ft) Ag. 34.29 gms / tonne Pb. 2.10% Zn 4.20%

51.0 - 52.1 = 1.1 m (3.6 ft) Ag. 41.49 gms / tonne Pb. 2.58% Zn 5.87%

59.4 - 81.1 = 21.7 m (71.2 ft)
Ag 69.35 gms / tonne
Pb 4.18%
Zn 6.62%



S. 3. 76 - S. 3. 76

ASSAY NUMBER	SECTION		CORE LENGTH (M)	ASSAYS		
	FROM (M)	TO (M)		Ag. ^{grams} _{ton}	Pb %	Zn %
	0.0	15.2	15.2	0.00	0.00	0.00
1751	15.2	16.8	1.6	133.0	8.17	10.82
	16.8	19.8	3.0	0.00	0.00	0.00

End of hole

LATITUDE 10631.975
 DEPARTURE 7680.82
 ELEVATION 1167.49
 DIP AT CORNER +7° 44'
 BEARING 136° 36' 21"
 DEPTH 19.8 m (32.15 ft)

15.2 - 16.8 = 1.6 m (5.25 ft) Ag. 133 grams/ton Pb 8.17% Zn 10.82%

E.C.I.

5.3.76 - 8.3.76

ASSAY NUMBER	SECTION		CORE LENGTH (M)	ASSAYS		
	FROM (M)	TO (M)		Ag ^{grams} / _{tonnes}	Pb %	Zn %
	0.0 ✓	10.1 ✓	10.1 ✓	0.00	0.00	0.00
1752	10.1 ✓	10.7 ✓	0.6	32.23 ✓	2.15 ✓	5.07 ✓
1753	10.7 ✓	12.2 ✓	1.5	49.37 ✓	2.10 ✓	4.98 ✓
1754	12.2 ✓	13.7 ✓	1.5	47.31 ✓	2.60 ✓	5.68 ✓
1755	13.7 ✓	15.2 ✓	1.5	97.72 ✓	4.70 ✓	13.68 ✓
1756	15.2 ✓	16.8 ✓	1.6	80.57 ✓	4.93 ✓	12.76 ✓
1757	16.8 ✓	18.3 ✓	1.5	86.74 ✓	4.80 ✓	10.26 ✓
1758	18.3 ✓	19.8 ✓	1.5	98.74 ✓	6.51 ✓	13.27 ✓
1759	19.8 ✓	21.3 ✓	1.5	99.77 ✓	6.36 ✓	13.12 ✓
1760	21.3 ✓	22.9 ✓	1.6	80.57 ✓	4.65 ✓	6.77 ✓
1761	22.9 ✓	24.4 ✓	1.5	24.34 ✓	1.43 ✓	1.68 ✓
1762	24.4 ✓	25.9 ✓	1.5	24.34 ✓	1.18 ✓	1.75 ✓
	25.9 ✓	53.3 ✓	27.4	0.00 ✓	0.00 ✓	0.00 ✓

End of hole

LATITUDE 10633.28 2N DIP AT SURFACE +9° 12"
 DEPARTURE 7681.65 69+10W BEARING 93° 23'
 ELEVATION 1167.74 DEPTH 53.3m (175ft)

10.1 - 22.9 = 12.9m (42.3ft)

Ag 77.26 grams / tonne

Pb 4.45%

Zn 9.76%

(E.C.I.)

ASSAY NUMBER	SECTION		CORE LENGTH	ASSAYS		
	FROM (M)	TO (M)		Ag. ^{grams} _{tonne}	Pb %	Zn %
	0.0 ✓	11.1 ✓	11.1	0.00 ✓	0.00 ✓	0.00 ✓
1763	11.1 ✓	12.2 ✓	1.1	33.24 ✓	2.35 ✓	5.52 ✓
1764	12.2 ✓	13.7 ✓	1.5	31.20 ✓	1.70 ✓	4.13 ✓
1765	13.7 ✓	15.2 ✓	1.5	76.80 ✓	4.63 ✓	11.80 ✓
1766	15.2 ✓	16.8 ✓	1.6	85.72 ✓	5.63 ✓	15.15 ✓
1767	16.8 ✓	18.3 ✓	1.5	46.29 ✓	2.48 ✓	6.28 ✓
1768	18.3 ✓	19.8 ✓	1.5	62.40 ✓	3.73 ✓	10.77 ✓
1769	19.8 ✓	21.3 ✓	1.5	60.34 ✓	3.45 ✓	7.99 ✓
1770	21.3 ✓	22.9 ✓	1.6	93.94 ✓	4.03 ✓	9.46 ✓
1771	22.9 ✓	24.4 ✓	1.5	104.92 ✓	6.20 ✓	12.50 ✓
1772	24.4 ✓	25.9 ✓	1.5	75.77 ✓	5.42 ✓	10.15 ✓
1773	25.9 ✓	27.4 ✓	1.5	71.66 ✓	4.25 ✓	6.02 ✓
1774	27.4 ✓	29.0 ✓	1.6	13.03 ✓	0.65 ✓	1.18 ✓
	29.0 ✓	85.3 ✓	56.3	0.00 ✓	0.00 ✓	0.00 ✓

End of hole.

LATITUDE 10632.55 2N DIP AT COLLAR +9°49'
 DEPARTURE 7681.265 6870W BEARING 103°49'
 ELEVATION 1167.83 DEPTH 85.3m (280ft)

11.1 - 27.4 = 16.3m (53.48ft)

Ag. 62.0 grams per ton
 Pb 4.04 %
 Zn 9.14 %

9. 3. 76. 10. 3. 76

ASSAY NUMBER	SECTION		CORE LENGTH (M)	ASSAYS		
	FROM (M)	TO (M)		gms Ag. tonne	Pb%	Zn%
1775	0.0 ✓	1.5 ✓	1.5	21.26 ✓	1.74 ✓	1.43 ✓
1776	1.5 ✓	3.0 ✓	1.5	17.14 ✓	1.18 ✓	1.30 ✓
1777	3.0 ✓	4.0 ✓	1.0	36.34 ✓	1.53 ✓	2.78 ✓
1778	4.0 ✓	6.1 ✓	2.1	3.09 ✓	0.14 ✓	0.08 ✓
1779	6.1 ✓	8.1 ✓	2.0	18.17 ✓	1.85 ✓	0.20 ✓
1780	8.1 ✓	9.5 ✓	1.4	24.34 ✓	1.95 ✓	2.43 ✓
1781	9.5 ✓	11.0 ✓	1.5	21.26 ✓	1.35 ✓	2.00 ✓
	11.0 ✓	17.2 ✓	6.2	NOT ASSAYED		
1782	17.2 ✓	20.2 ✓	3.0	13.03 ✓	1.18 ✓	1.43 ✓
1783	20.2 ✓	22.9 ✓	2.7	25.37 ✓	1.98 ✓	3.25 ✓
1784	22.9 ✓	25.9 ✓	3.0	6.17 ✓	0.65 ✓	1.15 ✓
1785	25.9 ✓	28.4 ✓	2.5	15.09 ✓	1.88 ✓	1.00 ✓
	28.4 ✓	38.9 ✓	10.5	NOT ASSAYED		
1786	38.9 ✓	41.0 ✓	2.1	8.91 ✓	0.58 ✓	1.83 ✓
1787	41.0 ✓	42.7 ✓	1.7	3.09 ✓	0.19 ✓	0.28 ✓
1788	42.7 ✓	44.4 ✓	1.7	122.06 ✓	7.59 ✓	13.05 ✓
	44.4 ✓	48.8 ✓	4.4	NOT ASSAYED		
1789	48.8 ✓	50.3 ✓	1.5	15.09 ✓	0.63 ✓	1.00 ✓
1790	50.3 ✓	51.8 ✓	1.5	75.77 ✓	4.75 ✓	5.45 ✓
1791	51.8 ✓	53.3 ✓	1.5	90.86 ✓	5.70 ✓	7.70 ✓
1792	53.3 ✓	54.9 ✓	1.6	82.63 ✓	4.90 ✓	8.77 ✓
1793	54.9 ✓	56.4 ✓	1.5	75.77 ✓	7.69 ✓	13.76 ✓
1794	56.4 ✓	57.9 ✓	1.5	67.54 ✓	4.48 ✓	6.42 ✓
1795	57.9 ✓	59.4 ✓	1.5	62.40 ✓	3.95 ✓	7.26 ✓
1796	59.4 ✓	61.0 ✓	1.6	78.86 ✓	4.30 ✓	6.94 ✓
1797	61.0 ✓	62.5 ✓	1.5	49.37 ✓	3.05 ✓	3.90 ✓
1798	62.5 ✓	64.0 ✓	1.5	36.34 ✓	1.85 ✓	2.10 ✓
1799	64.0 ✓	65.5 ✓	1.5	12.00 ✓	0.55 ✓	0.70 ✓
1800	65.5 ✓	67.1 ✓	1.6	50.40 ✓	2.55 ✓	1.58 ✓
1801	67.1 ✓	68.6 ✓	1.5	62.40 ✓	4.75 ✓	4.95 ✓
1802	68.6 ✓	70.1 ✓	1.5	43.54 ✓	2.30 ✓	2.28 ✓
1803	70.1 ✓	71.6 ✓	1.5	25.37 ✓	1.30 ✓	1.85 ✓
1804	71.6 ✓	73.2 ✓	1.6	25.37 ✓	1.78 ✓	3.23 ✓
1805	73.2 ✓	74.7 ✓	1.5	57.60 ✓	2.90 ✓	6.86 ✓
1806	74.7 ✓	76.2 ✓	1.5	44.23 ✓	2.23 ✓	4.70 ✓
1807	76.2 ✓	77.7 ✓	1.5	54.51 ✓	2.50 ✓	4.75 ✓

DDH U 38

Continued on Pages 84 & 85.

LATITUDE 3N 10767.245

DIP AT COLLAR $-73^{\circ} 15'$

DEPARTURE 74W 7588.402

BEARING $230^{\circ} 24' 17''$

ELEVATION 1144.623

DEPTH 110.3 m. (362 ft).

$$\underline{50.3 - 96.5 = 46.2 \text{ m (151.6 ft)}}$$

Ag 60.21 grams per tonne

Pb 3.68%

Zn 6.57%

$$\underline{42.7 - 96.5 = 53.8 \text{ m (176.5 ft)}}$$

Ag 55.98 grams per tonne

Pb 3.42%

Zn 6.08%

ASSAY NUMBER	SECTION		CORE LENGTH	ASSAYS		
	FROM (m)	TO (m)		Ag ^{grams} / _{tonne}	Pb %	Zn %
1808.	77.7 ✓	79.2 ✓	1.5	100.8 ✓	3.48 ✓	7.68 ✓
1809	79.2 ✓	80.8 ✓	1.6	45.26 ✓	2.90 ✓	5.75 ✓
1810	80.8 ✓	82.3 ✓	1.5	125.14 ✓	7.36 ✓	16.65 ✓
1811	82.3 ✓	83.8 ✓	1.5	129.94 ✓	8.28 ✓	14.95 ✓
1812	83.8 ✓	85.3 ✓	1.5	80.57 ✓	5.10 ✓	8.24 ✓
1813	85.3 ✓	86.9 ✓	1.6	59.31 ✓	4.68 ✓	7.88 ✓
1814	86.9 ✓	88.4 ✓	1.5	41.49 ✓	2.80 ✓	5.15 ✓
1815	88.4 ✓	89.9 ✓	1.5	44.23 ✓	2.90 ✓	4.80 ✓
1816	89.9 ✓	91.4 ✓	1.5	28.46 ✓	1.25 ✓	2.13 ✓
1817	91.4 ✓	93.0 ✓	1.6	60.34 ✓	3.88 ✓	2.95 ✓
1818	93.0 ✓	94.5 ✓	1.5	36.34 ✓	2.15 ✓	13.32 ✓
1819	94.5 ✓	96.5 ✓	2.0	60.34 ✓	4.08 ✓	11.03 ✓
	96.5 ✓	110.3 ✓	13.8	0.00 ✓	0.00 ✓	0.00 ✓

End of hole

42.7 - 96.5 = 53.8 m (176.5 ft)
 Ag 55.98 grams per tonne
 Pb 3.42 %
 Zn 6.08 %

50.3 - 96.5 = 46.2 m (151.6 ft)
 Ag 60.21 grams per tonne
 Pb 3.68 %
 Zn 6.57 %

10.3.76 - 12.3.76

ASSAY NUMBER	SECTION		CORE LENGTH	ASSAYS		
	FROM (m)	TO (m)		Ag. ^{grams} / ton	Pb (%)	Zn (%)
	0.0	42.7	42.7	0.00	0.00	0.00
1820	42.7	43.4	0.7	5.14	0.07	0.48
1821	43.4	45.0	1.6	85.72	6.10	9.92
1822	45.0	46.7	1.7	95.66	6.10	9.20
	46.7	54.7	8.0	NOT ASSAYED		
1823	54.7	56.2	1.5	60.34	2.23	4.03
	56.2	57.8	1.6	NOT ASSAYED		
1824	57.8	59.4	1.6	93.94	5.20	7.17
1825	59.4	61.0	1.6	8.23	0.48	0.70
1826	61.0	62.5	1.5	102.86	6.15	10.43
1827	62.5	64.0	1.5	58.63	3.70	6.15
1828	64.0	65.5	1.5	37.37	1.55	1.70
1829	65.5	67.1	1.6	61.37	3.20	5.20
1830	67.1	68.6	1.5	55.54	3.75	7.50
1831	68.6	70.1	1.5	85.72	2.98	6.66
1832	70.1	71.6	1.5	92.92	3.90	6.62
1833	71.6	73.2	1.6	98.74	4.80	7.55
1834	73.2	74.7	1.5	117.94	5.18	8.40
	74.7	85.8	11.1	NOT ASSAYED		
1835	85.8	88.4	2.6	8.91	0.43	0.93
1836	88.4	89.9	1.5	5.14	0.15	0.75
1837	89.9	91.4	1.5	12.00	0.30	1.70
1838	91.4	93.0	1.6	32.23	1.68	2.95
1839	93.0	94.5	1.5	37.37	1.68	3.10
1840	94.5	96.0	1.5	13.03	0.80	4.10
1841	96.0	97.5	1.5	20.23	1.43	2.53
1842	97.5	99.1	1.6	5.14	0.08	0.65
1843	99.1	100.6	1.5	8.91	0.35	1.50
1844	100.6	102.1	1.5	90.86	4.50	12.71
1845	102.1	103.6	1.5	106.97	6.90	10.86
1846	103.6	104.6	1.0	22.29	0.99	3.20
	104.6	108.8	4.2	0.00	0.00	0.00

End of hole

LATITUDE 3N 10767.051
 DEPARTURE 14W. 7588.308
 ELEVATION 1144.623

DIP AT COLLAR -53° 58'
 BEARING 225° 20' 45"
 DEPTH 108.8m (357ft)

43.4 - 46.7 = 3.3m (10.8ft) Pb. 6.10%

Ag. 90.84 grams per tonne. Zn. 9.55%

54.7 - 74.7 = 20.0m (65.6ft)

Ag. 66.83 grams per tonne

Pb 3.38%

57.8 - 74.7 = 16.9m (55.5ft)

Ag. 73.73 grams per tonne

Pb 3.80%

Zn. 6.16%

Zn. 5.51%

100.6 - 103.6 = 3.0m (9.84ft) Pb 5.70%

Ag. 98.97 grams per tonne Zn. 11.79%

E.C.J.

12.3.76 - 15.3.76

ASSAY NUMBER	SECTION		CORE LENGTH (M)	ASSAYS		
	FROM (M)	TO (M)		Ag ^{grams} / _{tonne}	Pb %	Zn %
	0.0 ✓	57.9 ✓	57.9	0.00	0.00	0.00
1847	57.9 ✓	61.0 ✓	3.1	24.84 ✓	2.02 ✓	3.50 ✓
1848	61.0 ✓	63.7 ✓	2.7	25.37 ✓	1.90 ✓	3.15 ✓
	63.7 ✓	87.3 ✓	23.6	NOT ASSAYED		
1849	87.3 ✓	88.4 ✓	1.1	93.94 ✓	6.08 ✓	10.07 ✓
1850	88.4 ✓	89.9 ✓	1.5	90.86 ✓	5.48 ✓	7.58 ✓
1851	89.9 ✓	91.4 ✓	1.5	118.97 ✓	7.81 ✓	9.91 ✓
1852	91.4 ✓	93.0 ✓	1.6	62.40 ✓	3.60 ✓	9.25 ✓
1853	93.0 ✓	96.0 ✓	3.0	9.94 ✓	0.59 ✓	1.05 ✓
	96.0 ✓	97.5 ✓	1.5	0.00	0.00	0.00

End of hole

796

LATITUDE (BN) 10769.061
 DEPARTURE (WN) 7590.681
 ELEVATION 1144.623

DIP AT COLLAR -46° 19'
 BEARING 44° 25' 21"
 DEPTH 97.51m (320 ft)

87.3 - 93.0 = 5.7m (18.7 ft)
 Ag 90.86 grams / tonne
 Pb 5.76%
 Zn 9.14%

(E.C.J.)

15.3.76 - 16.3.76

ASSAY NUMBER	SECTION		CORE LENGTH	ASSAYS		
	FROM (m)	TO (m)		Ag. ^{grams} / _{tonne}	Pb %	Zn %
1854	0.0 ✓	3.0 ✓	3.0	13.03 ✓	0.93 ✓	1.38 ✓
1855	3.0 ✓	6.1 ✓	3.1	12.00 ✓	0.79 ✓	1.23 ✓
1856	6.1 ✓	7.3 ✓	1.2	13.03 ✓	0.90 ✓	0.83 ✓
1857	7.3 ✓	9.1 ✓	1.8	10.63 ✓	5.95 ✓	5.49 ✓
1858	9.1 ✓	10.7 ✓	1.6	42.51 ✓	2.85 ✓	4.75 ✓
1859	10.7 ✓	12.2 ✓	1.5	62.40 ✓	4.10 ✓	7.98 ✓
1860	12.2 ✓	13.7 ✓	1.5	87.77 ✓	6.41 ✓	9.94 ✓
1861	13.7 ✓	15.2 ✓	1.5	45.26 ✓	3.45 ✓	4.65 ✓
1862	15.2 ✓	16.8 ✓	1.6	19.20 ✓	1.14 ✓	2.00 ✓
1863	16.8 ✓	18.3 ✓	1.5	36.34 ✓	2.60 ✓	4.73 ✓
1864	18.3 ✓	19.8 ✓	1.5	27.43 ✓	2.00 ✓	3.85 ✓
1865	19.8 ✓	21.3 ✓	1.5	12.00 ✓	0.68 ✓	1.35 ✓
1866	21.3 ✓	22.9 ✓	1.6	31.20 ✓	2.20 ✓	3.50 ✓
1867	22.9 ✓	24.4 ✓	1.5	30.17 ✓	2.13 ✓	4.00 ✓
1868	24.4 ✓	25.9 ✓	1.5	22.29 ✓	1.58 ✓	1.90 ✓
1869	25.9 ✓	27.4 ✓	1.5	18.17 ✓	1.25 ✓	1.80 ✓
1870	27.4 ✓	29.0 ✓	1.6	42.51 ✓	2.70 ✓	3.90 ✓
1871	29.0 ✓	30.5 ✓	1.5	91.89 ✓	6.33 ✓	12.51 ✓
1872	30.5 ✓	32.0 ✓	1.5	82.63 ✓	4.90 ✓	9.00 ✓
1873	32.0 ✓	33.8 ✓	1.8	156.34 ✓	8.98 ✓	18.92 ✓
	33.8 ✓	53.3 ✓	19.5	0.00	0.00	0.00

End of hole

LATITUDE 3N. 10767.689.
 DEPARTURE 14W. 7590.105
 ELEVATION 1148.632

DIP AT COLLAR + 68° 18'
 BEARING 45° 29' 33"
 DEPTH 53.3 m (175 ft).

7.3m - 15.2m = 7.9m (26ft).

Ag 82.2 grams/tonne.
 Pb 4.58%
 Zn 6.50%

7.3m - 18.3m = 11.0m (36ft)
 Ag 66.78 grams per tonne
 Pb 5.30%
 Zn 5.60%

7.3m - 33.8m = 26.5m (87ft)

Ag 58.9 grams per tonne.
 Pb 4.18%
 Zn 5.33%

29.0m - 33.8m = 4.8m (15.74ft).

Ag 113.17 grams per tonne, Pb 6.88%
 Zn 10.07%

16.3.76 - 17.3.76

ASSAY NUMBER	SECTION		CORE		ASSAYS	
	FROM (m)	TO (m)	LENGTH (m)	Wt. (gms)	Wt. (gms)	Wt. (gms)
1874	0.0	3.0	3.0	8.0	14.06	1.75
1875	3.0	5.0	2.0	17.14	1.35	1.40
	5.0	6.6	1.6			
				NOT ASSAYED		
1876	6.6	9.1	2.5	35.31	2.88	3.00
1877	9.1	10.7	1.6	53.49	4.55	5.81
1878	10.7	12.2	1.5	72.69	4.78	8.14
1879	12.2	13.7	1.5	166.29	10.78	19.02
1880	13.7	15.2	1.5	173.49	11.93	21.05
1881	15.2	16.8	1.6	145.03	9.80	18.15
1882	16.8	18.3	1.5	224.92	12.61	21.91
1883	18.3	19.8	1.5	177.60	14.30	22.73
1884	19.8	21.3	1.5	115.89	8.05	12.76
1885	21.3	22.9	1.6	143.32	9.43	16.24
1886	22.9	24.6	1.7	117.94	7.28	13.87
1887	24.6	25.4	0.8	4.11	0.15	0.30
	25.4	45.7	20.3	0.00	0.00	0.00

End of hole

Ag 177 grams stain
 Pb 11.99g
 Zn 13.54g

12.2 - 19.8 = 7.6m (25ft)

Ag 123.97 grams for stain
 Pb 8.41g
 Zn 14.05g

6.6m - 24.6 = 18.0m (59ft)

Latitude: 10767.235 SN DIF AT CORNER + 89° 15'
 DEPARTURE 7589.511 74W BEARING 206° 33' 54"
 ELEVATION 1148.756 DEPTH 45.7m (150ft)

ASSAY NUMBER	SECTION		CORE LENGTH (M)	ASSAYS		
	FROM (M)	TO (M)		Ag ^{grams} / _{tonne}	Pb%	Zn%
1888	0.0	3.0	3.0	17.14	1.23	1.70
1889	3.0	4.6	1.6	29.14	2.43	2.40
1890	4.6	6.1	1.5	25.87	2.20	3.20
1891	6.1	7.6	1.5	52.46	4.35	5.19
1892	7.6	9.1	1.5	48.34	3.90	7.17
1893	9.1	10.7	1.6	40.46	3.10	6.18
1894	10.7	12.2	1.5	31.20	1.93	3.33
1895	12.2	13.7	1.5	114.17	7.74	12.24
1896	13.7	15.2	1.5	169.37	10.86	16.86
1897	15.2	16.8	1.6	89.83	6.16	13.86
1898	16.8	18.3	1.5	60.34	3.90	5.85
1899	18.3	19.8	1.5	133.03	8.60	15.24
	19.8	33.4	13.6 m	NOT ASSAYED.		
1900	33.4	34.8	1.4	21.36	1.85	1.15
1901	34.8	36.1	1.3	89.83	7.37	5.95
	36.1	45.7	9.6	0.00	0.00	0.00

End of Hole.

LATITUDE 10767.80 3N DIP AT COLLAR +60° 46'
 DEPARTURE 7587.31 74W BEARING 235° 57'
 ELEVATION 1148.79 DEPTH 45.7 m (150 ft)

61 m - 19.8 m = 41.2 m (135 ft)
 Ag 81.87 grams per tonne
 Pb 5.60 %
 Zn 9.55 %

34.8 m - 36.1 m = 1.3 m (4.27 ft) Ag 89.83 gms/tonne Pb 7.37% Zn 5.95%

18.3.76 - 19.3.76

ASSAY NUMBER	SECTION		CORE LENGTH (M)	ASSAYS		
	From (m)	To (m)		Ag. ^{grams} / tonne	Pb%	Zn%
1902	0.0 ✓	1.5 ✓	1.5	48.34	2.75	6.25
1903	1.5 ✓	3.0 ✓	1.5	65.49	4.68	6.68
1904	3.0 ✓	4.6 ✓	1.6	75.17	7.19	5.74
1905	4.6 ✓	6.1 ✓	1.5	53.49	4.40	4.60
1906	6.1 ✓	7.6 ✓	1.5	97.12	6.47	11.27
1907	7.6 ✓	9.1 ✓	1.5	39.43	2.37	7.01
1908	9.1 ✓	11.0 ✓	1.9	48.34	2.80	5.79
1909	11.0 ✓	12.9 ✓	1.9	1.03	0.03	0.18
1910	12.9 ✓	14.4 ✓	1.5	54.51	3.90	6.65
1911	14.4 ✓	16.2 ✓	1.8	38.40	2.30	6.48
	16.2 ✓	34.3 ✓	18.1	NOT ASSAYED		
1912	34.3 ✓	35.1 ✓	0.8	1.03	0.04	0.13
1913	35.1 ✓	36.6 ✓	1.5	94.63	5.81	11.17
1914	36.6 ✓	38.1 ✓	1.5	26.40	1.65	2.70
1915	38.1 ✓	39.6 ✓	1.5	49.37	3.53	6.10
1916	39.6 ✓	41.3 ✓	1.7	68.57	5.44	5.54
	41.3 ✓	45.7 ✓	4.4	NOT ASSAYED		
1917	45.7 ✓	47.2 ✓	1.5	40.46	2.83	3.30
1918	47.2 ✓	48.8 ✓	1.6	92.92	6.64	7.32
1919	48.8 ✓	50.3 ✓	1.5	114.17	7.67	13.16
1920	50.3 ✓	51.8 ✓	1.5	94.63	5.86	4.90
1921	51.8 ✓	53.3 ✓	1.5	98.74	6.15	9.70
1922	53.3 ✓	54.9 ✓	1.6	122.06	8.44	13.26
1923	54.9 ✓	56.4 ✓	1.5	69.60	4.03	5.79
1924	56.4 ✓	57.9 ✓	1.5	16.11	1.28	2.10
1925	57.9 ✓	59.4 ✓	1.5	7.2	0.40	0.83
	59.4 ✓	61.5 ✓	2.1	NOT ASSAYED		
1926	61.5 ✓	62.5 ✓	1.0	18.17	1.34	1.38

End of hole

LATITUDE 6N
DEPARTURE 74W
ELEVATION

DIP AT COLLAR
BEARING
LENGTH 62.5 m (205 ft)

0m - 16.2m = 16.2m (53 ft)
Ag 50.78 grams per tonne
Pb 3.57%
Zn 5.92%

35.1m - 41.3m = 6.2m (20.34 ft)
Ag 59.54 grams per tonne
Pb 4.15%
Zn 6.35%

35.1m - 56.4m = 21.3m (70 ft)
Ag 62.89 grams per tonne
Pb 4.21%
Zn 6.20%

45.7 - 56.4 = 10.7m (35 ft)
Ag 90.69 grams per tonne
Pb 5.98%
Zn 8.66%

19.3.76 - 19.3.76

ASSAY NUMBER	SECTION		CORE LENGTH (m)	ASSAYS		
	From (m)	To (m)		Ag ^{Grams} _{tonne}	Pb (%)	Zn (%)
1927	0.0 ✓	2.1 ✓	2.1	97.12 ✓	5.76 ✓	10.87 ✓
1928	2.1 ✓	4.1 ✓	2.0	29.14 ✓	1.78 ✓	2.48 ✓
1929	4.1 ✓	5.5 ✓	1.4	75.77 ✓	4.38 ✓	7.86 ✓
1930	5.5 ✓	7.4 ✓	1.9	18.86 ✓	5.00 ✓	9.15 ✓
1931	7.4 ✓	10.0 ✓	2.6	15.09 ✓	0.97 ✓	3.00 ✓
1932	10.0 ✓	11.1 ✓	1.1	88.80 ✓	5.64 ✓	9.80 ✓
1933	11.1 ✓	12.4 ✓	1.3	13.03 ✓	0.63 ✓	3.03 ✓
	12.4 ✓	14.2 ✓	1.8	NOT ASSAYED		
1934	14.2 ✓	15.5 ✓	1.3	60.34 ✓	3.60 ✓	5.55 ✓
1935	15.5 ✓	16.8 ✓	1.3	5.14 ✓	0.23 ✓	0.35 ✓
	16.8 ✓	41.2 ✓	24.4	NOT ASSAYED		
1936	41.2 ✓	42.7 ✓	1.5	45.26 ✓	2.68 ✓	3.35 ✓
1937	42.7 ✓	44.2 ✓	1.5	51.43 ✓	3.13 ✓	2.40 ✓
1938	44.2 ✓	45.7 ✓	1.5	68.57 ✓	4.55 ✓	4.05 ✓
1939	45.7 ✓	46.9 ✓	1.2	65.49 ✓	4.20 ✓	3.40 ✓
	46.9 ✓	49.1 ✓	2.2	NOT ASSAYED		
1940	49.1 ✓	51.4 ✓	2.3	21.26 ✓	1.35 ✓	1.98 ✓
	51.4 ✓	60.7 ✓	9.3	NOT ASSAYED		
1941	60.7 ✓	62.5 ✓	1.8	111.09 ✓	6.64 ✓	10.77 ✓
1942	62.5 ✓	64.0 ✓	1.5	99.77 ✓	4.80 ✓	7.14 ✓
1943	64.0 ✓	65.5 ✓	1.5	74.74 ✓	3.45 ✓	5.87 ✓
1944	65.5 ✓	67.1 ✓	1.6	79.54 ✓	5.44 ✓	8.64 ✓
1945	67.1 ✓	68.6 ✓	1.5	83.66 ✓	5.50 ✓	9.50 ✓
1946	68.6 ✓	70.1 ✓	1.5	73.71 ✓	4.28 ✓	8.49 ✓
1947	70.1 ✓	71.1 ✓	1.0	100.80 ✓	5.50 ✓	10.47 ✓
	71.1 ✓	83.8 ✓	12.7	0.00	0.00	0.00

End of hole

LATITUDE 6N
DEPARTURE 74W
ELEVATION.

DIP AT COLLAR
BEARING.
DEPTH 83.8 m (275 ft)

0.0 - 11.1 = 11.1m (36.4 ft)

Ag 60.0 grams per ton
Pb 3.60 %
Zn 6.73 %

0.0 - 15.5 = 15.5m (50.85 ft)

Ag 49.13 grams per tonne
Pb 2.93 %
Zn 5.54 %

41.2m - 46.9m = 5.7m (18.7 ft)

Ag 57.28
Pb 3.61 %
Zn 3.29 %

Combined Pb, Zn = 6.90 %

LOW

60.7 - 71.1 = 10.4m (34.12 ft)

Ag 89.02 grams per tonne
Pb 5.12 %
Zn 8.67 %

DPH U. 47.

ASSAY NUMBER

SECTION

Core

ASSAYS

From (m) / (m) LENGTH

Ag. grams

Pb

Zn

ASSAYS

21.3-76 - 22.3-76

End of hole

1948	6.0	1.8	1.8	135.00	9.97	9.80
1949	1.8	3.0	1.2	87.77	7.64	6.71
1950	3.0	5.0	2.0	48.84	4.40	2.35
1951	5.0	6.4	1.4	26.40	1.68	2.40
1952	6.4	8.3	1.9	7.20	0.39	0.95
1953	8.3	9.1	0.8	39.43	4.20	1.80
1954	9.1	10.7	1.6	44.22	4.53	2.45
1955	10.7	12.2	1.5	53.49	4.10	5.88
1956	12.2	13.7	1.5	54.51	3.43	6.36
1957	13.7	15.0	1.3	45.26	2.63	4.30
1958	15.0	16.8	1.8	133.03	8.20	14.39
1959	16.8	18.3	1.5	146.06	8.60	14.73
1960	18.3	19.8	1.5	125.14	6.95	21.00
1961	19.8	21.3	1.5	123.09	7.90	20.19
1962	21.3	22.2	0.9	209.83	11.45	26.28
1963	22.2	29.5	7.3	ASSAYED	0.19	0.10
1963	29.5	30.3	0.8	0.69	0.15	0.15
1964	30.3	31.3	1.0	41.49	2.75	3.48
1965	31.3	32.9	1.6	112.12	6.92	12.45
1966	32.9	34.4	1.5	63.46	4.28	9.82
1967	34.4	37.6	3.2	NOT ASSAYED	4.13	5.49
1967	37.6	39.5	1.9	58.63	4.13	5.49
1968	39.5	57.5	18.0	NOT ASSAYED	7.40	7.40
1968	57.5	59.4	1.9	22.63	6.22	7.40
1969	59.4	61.0	1.6	58.63	3.48	4.20
1970	61.0	62.5	1.5	85.72	6.92	7.79
1971	62.5	64.0	1.5	112.12	6.75	11.03
1972	64.0	65.5	1.5	22.63	3.68	6.23
1972	65.5	80.8	15.3	0.00	0.00	0.00

LITHOLOGY DEPTH

DEPTH

TIP AT CORNER

BEARING

DEPTH 80.8 m (265 ft)

0 - 22.2 = 22.5 m (73 ft)

Ag 82.80 grams per ton

Pb 5.55

Zn 9.14

15.0 - 22.2 = 7.2 m (23.6 ft)

Ag 141.63 grams per ton

Pb 8.37

Zn 19.16

0.0 - 39.5 = 39.5 m (129.6 ft)

Ag 57.37 grams per ton

Pb 3.83

Zn 6.37

31.3 - 34.4 = 3.1 m (10.17 ft)

Ag 88.56 grams per ton

Pb 5.64

Zn 11.18

0.0 - 65.5 = 65.5 m (215 ft)

Ag 44.85 grams per ton

Pb 2.96

Zn 4.73

57.5 - 65.5 = 8.0 m (26.25 ft)

Ag 83.94 grams per ton

Pb 5.32

Zn 7.28

22. 3. 76 - 23. 3. 76

ASSAY NUMBER	SECTION		CORE LENGTH (M)	ASSAYS		
	FROM (M)	TO (M)		Ag ^{frames} - ton	Pb %	Zn %
1973	0 ✓	1.5 ✓	1.5	93.94 ✓	4.93 ✓	9.76 ✓
1974	1.5 ✓	2.9 ✓	1.4	121.03 ✓	8.85 ✓	7.27 ✓
1975	2.9 ✓	4.6 ✓	1.7	80.57 ✓	6.95 ✓	3.10 ✓
1976	4.6 ✓	6.1 ✓	1.5	57.60 ✓	4.88 ✓	3.60 ✓
1977	6.1 ✓	8.1 ✓	2.0	49.37 ✓	2.98 ✓	5.21 ✓
1978	8.1 ✓	10.7 ✓	2.6	22.29 ✓	1.09 ✓	2.39 ✓
1979	10.7 ✓	12.2 ✓	1.5	29.14 ✓	1.60 ✓	2.95 ✓
1980	12.2 ✓	14.5 ✓	2.3	40.46 ✓	2.68 ✓	4.48 ✓
	14.5	22.3	7.8	NOT ASSAYED		
1981	22.3 ✓	24.4 ✓	2.1	55.54 ✓	2.70 ✓	6.31 ✓
1982	24.4 ✓	25.9 ✓	1.5	90.86 ✓	4.40 ✓	9.74 ✓
1983	25.9 ✓	27.2 ✓	1.3	55.54 ✓	2.98 ✓	6.97 ✓
	27.2	28.7	1.5	NOT ASSAYED		
1984	28.7 ✓	29.8 ✓	1.1	26.40 ✓	1.74 ✓	4.48 ✓
1985	29.8 ✓	31.1 ✓	1.3	33.26 ✓	2.48 ✓	6.26 ✓
	31.1	32.1	1.0	NOT ASSAYED		
1986	32.1 ✓	35.1 ✓	3.0	43.54 ✓	2.40 ✓	4.90 ✓
1987	35.1 ✓	38.1 ✓	3.0	45.26 ✓	2.68 ✓	6.54 ✓
1988	38.1 ✓	39.6 ✓	1.5	85.72 ✓	5.87 ✓	10.03 ✓
1989	39.6 ✓	41.1 ✓	1.5	157.37 ✓	10.13 ✓	12.15 ✓
1990	41.1 ✓	42.7 ✓	1.6	77.83 ✓	4.95 ✓	11.34 ✓
1991	42.7 ✓	44.2 ✓	1.5	112.12 ✓	7.80 ✓	14.06 ✓
1992	44.2 ✓	46.2 ✓	2.0	23.31 ✓	1.30 ✓	1.55 ✓
1993	46.2 ✓	48.0 ✓	1.8	8.91 ✓	0.58 ✓	1.20 ✓
	48.0	61.5	13.5	NOT ASSAYED		
1994	61.5 ✓	64.0 ✓	2.5	4.11 ✓	0.33 ✓	1.63 ✓
1995	64.0 ✓	65.5 ✓	1.5	10.97 ✓	1.40 ✓	2.63 ✓
1996	65.5 ✓	67.1 ✓	1.6	18.17 ✓	1.20 ✓	2.40 ✓
1997	67.1 ✓	68.6 ✓	1.5	130.97 ✓	7.49 ✓	13.76 ✓
1998	68.6 ✓	70.5 ✓	1.9	54.51 ✓	3.10 ✓	5.10 ✓
1999	70.5 ✓	73.2 ✓	2.7	50.40 ✓	3.43 ✓	4.70 ✓
2000	73.2 ✓	74.7 ✓	1.5	104.92 ✓	6.99 ✓	12.08 ✓
2001	74.7 ✓	76.2 ✓	1.5	111.09 ✓	6.02 ✓	10.65 ✓
2002	76.2 ✓	77.7 ✓	1.5	84.69 ✓	5.41 ✓	9.07 ✓
2003	77.7 ✓	80.8 ✓	3.1	19.20 ✓	1.20 ✓	1.13 ✓
	80.8	120.7	39.9	0.00	0.00	0.00

End of hole.

LATITUDE 10826.65 ON DIP AT COLLAR -55° 30'
 DEPARTURE 7645.32 14W BEARING 214° 35' 53"
 ELEVATION 1143.330 DEPTH 120.7 m. (396 ft)

0 - 14.5 = 14.5 m (47.6 ft)

Ag 57.05 grams per tonne.

Pb 3.88%

Zn 4.61%

0 - 27.2 = 27.2 m (89.0 ft)

Ag 42.36 grams per tonne

Pb 2.66% } LOW!

Zn 3.82% }

22.3 - 27.2 = 4.9 m (16.0 ft)

Ag 66.35 gms per tonne Pb 3.29%

Zn 1.53%

0 - 44.2 = 44.2 m (145 ft)

Ag 48.6 g/t.

Pb 3.09%

Zn 5.06%

28.7 - 31.1 = 2.4 m (8.0 ft)

Ag 30.12 gms per tonne, Pb 2.14%

Zn 5.44%

32.1 - 44.2 = 12.1 m (40 ft)

Ag 75.72 g/t.

Pb 4.86%

Zn 8.83%

67.1 - 77.7 = 10.6 m (34.78 ft)

Ag 83.69 g/t.

Pb 5.17%

Zn 8.56%

(E.C.J.)

24.3.76 - 25.3.76

ASSAY NUMBER	SECTION		CORE LENGTH (M)	ASSAYS		
	FROM (M)	TO (M)		Ag ^{grams} _{ounce}	Pb (%)	Zn (%)
2004	0.0 ✓	1.5 ✓	1.5	35.31 ✓	2.08 ✓	3.80 ✓
2005	1.5 ✓	4.7 ✓	3.2	21.26 ✓	1.28 ✓	2.55 ✓
2006	4.7 ✓	6.1 ✓	1.4	32.23 ✓	2.05 ✓	3.90 ✓
2007	6.1 ✓	7.6 ✓	1.5	35.31 ✓	2.28 ✓	3.85 ✓
2008	7.6 ✓	9.1 ✓	1.5	17.14 ✓	0.93 ✓	1.60 ✓
2009	9.1 ✓	12.2 ✓	3.1	21.26 ✓	1.65 ✓	4.85 ✓
2010	12.2 ✓	13.7 ✓	1.5	25.37 ✓	1.75 ✓	3.60 ✓
2011	13.7 ✓	15.3 ✓	1.6	31.20 ✓	2.28 ✓	3.20 ✓
2012	15.3 ✓	16.7 ✓	1.4	31.20 ✓	2.10 ✓	3.30 ✓
2013	16.7 ✓	18.2 ✓	1.5	27.43 ✓	1.73 ✓	2.78 ✓
2014	18.2 ✓	19.8 ✓	1.6	42.51 ✓	2.25 ✓	5.60 ✓
2015	19.8 ✓	21.3 ✓	1.5	53.49 ✓	2.95 ✓	9.63 ✓
	21.3 ✓	76.2 ✓	54.9	NOT ASSAYED		
2016	76.2 ✓	77.7 ✓	1.5	33.26 ✓	2.15 ✓	5.15 ✓
2017	77.7 ✓	79.2 ✓	1.5	20.23 ✓	1.65 ✓	2.15 ✓
2018	79.2 ✓	80.7 ✓	1.5	12.00 ✓	1.35 ✓	0.38 ✓
2019	80.7 ✓	82.3 ✓	1.6	10.97 ✓	1.35 ✓	0.20 ✓

End of hole

961

LATITUDE 10825.927 6N DIP AT COLLAR + 00° 50'
 DEPARTURE 7643.088 74W BEARING 222° 39' 01"
 ELEVATION 1144.542 DEPTH 82.3m. (270ft)

18.2m - 21.3m = 3.1m (10.0ft)
 Ag 47.82 g/t. Pb 2.59% Zn 7.55%

76.2m - 77.7m = 1.5m (5ft)
 Ag 33.26 g/t. Pb 2.15% Zn 5.15%

E.C.J.

25.3.76 . 26.3.76

ASSAY NUMBER	SECTION		CORE LENGTH (m)	ASSAYS		
	FROM (m)	TO (m)		Ag ^{grams per tonne}	Pb (%)	Zn (%)
2026	0.0 ✓	3.0 ✓	3.0	43.54 ✓	2.05 ✓	3.68 ✓
2027	3.0 ✓	6.1 ✓	3.1	17.14 ✓	1.30 ✓	2.15 ✓
2028	6.1 ✓	9.1 ✓	3.0	25.37 ✓	1.50 ✓	3.83 ✓
2029	9.1 ✓	10.7 ✓	1.6	14.06 ✓	0.80 ✓	1.75 ✓
	10.7 ✓	12.2 ✓	1.5	NOT ASSAYED		
2030	12.2 ✓	13.7 ✓	1.5	150.17 ✓	9.72 ✓	12.48 ✓
2031	13.7 ✓	15.2 ✓	1.5	44.23 ✓	2.93 ✓	3.30 ✓
2032	15.2 ✓	16.8 ✓	1.6	52.46 ✓	3.20 ✓	3.95 ✓
2033	16.8 ✓	18.3 ✓	1.5	136.12 ✓	7.57 ✓	11.31 ✓
2034	18.3 ✓	19.8 ✓	1.5	147.09 ✓	7.87 ✓	11.46 ✓
2035	19.8 ✓	21.3 ✓	1.5	41.49 ✓	2.38 ✓	3.75 ✓
2036	21.3 ✓	22.9 ✓	1.6	49.87 ✓	2.93 ✓	5.86 ✓
2037	22.9 ✓	24.4 ✓	1.5	58.63 ✓	3.38 ✓	7.09 ✓
2038	24.4 ✓	25.9 ✓	1.5	75.77 ✓	4.25 ✓	7.59 ✓
2039	25.9 ✓	27.4 ✓	1.5	77.83 ✓	4.70 ✓	7.85 ✓
2040	27.4 ✓	30.5 ✓	3.1	44.23 ✓	2.65 ✓	4.30 ✓
2041	30.5 ✓	32.0 ✓	1.5	80.57 ✓	5.31 ✓	10.55 ✓
	32.0 ✓	42.7 ✓	10.7	NOT ASSAYED		
2042	42.7 ✓	45.7 ✓	3.0	30.17 ✓	2.18 ✓	2.55 ✓
2043	45.7 ✓	48.8 ✓	3.1	62.40 ✓	5.71 ✓	2.80 ✓
2044	48.8 ✓	50.3 ✓	1.5	36.34 ✓	2.90 ✓	1.40 ✓
	50.3 ✓	88.3 ✓	38.0 38.0	NOT ASSAYED		
2045	88.3 ✓	91.4 ✓	3.1	17.14 ✓	1.65 ✓	1.10 ✓

End of hole

LATITUDE 108 25.601 LN
 DEPARTURE 7643.895
 ELEVATION 1144.519
 DIP AT COLLAR +00° 37'
 BEARING 189° 02' 53"
 DEPTH 91.4 m (300 ft)

12.2 - 32.0 = 19.8 m (65 ft)

Ag 76.66 m/t
 Pb 4.55 %
 Zn 7.18 %

45.7 - 48.8 = 3.1 m ^(10 ft) Ag 62.40 g/t
 Pb 5.71 % Zn 2.80 %

E.C.J.

26.3.76 - 27.3.76

ASSAY NUMBER	SECTION		CORE LENGTH (M)	ASSAYS		
	FROM (M)	TO (M)		Ag. ^{found} _{found}	Pb%	Zn%
2020	0.0	1.5	1.5	35.31	2.10	4.45
2021	1.5	3.0	1.5	49.37	3.20	10.14
2022	3.0	4.5	1.5	56.57	3.15	6.93
2023	4.5	6.0	1.5	46.29	2.93	4.10
2024	6.0	7.6	1.6	44.23	2.45	4.20
2025	7.6	9.1	1.5	25.37	1.60	2.90
2046	9.1	10.6	1.5	30.17	1.53	3.75
2047	10.6	12.1	1.5	25.37	1.68	1.28
2048	12.1	13.7	1.6	23.31	1.48	1.43
2049	13.7	15.2	1.5	38.40	2.65	2.30
	15.2	22.9	7.7	NOT ASSAYED		
2050	22.9	24.3	1.4	74.74	3.93	5.39
2051	24.3	25.9	1.6	28.46	1.95	5.14
2052	25.9	27.4	1.5	42.51	2.75	7.93
2053	27.4	28.9	1.5	33.31	2.20	3.50
2054	28.9	30.5	1.6	17.14	1.08	2.50
2055	30.5	32.0	1.5	20.23	1.58	1.68
2056	32.0	33.5	1.5	14.06	1.08	1.83
2057	33.5	35.0	1.5	13.03	0.65	1.45
2058	35.0	36.5	1.5	31.20	1.88	1.55
2059	36.5	38.0	1.5	55.54	3.18	6.62
2060	38.0	39.6	1.6	30.17	1.65	2.83
2061	39.6	41.1	1.5	48.74	5.61	8.99
2084	41.1	41.6	0.5	94.63	6.30	10.14
	41.6	70.1	28.5	0.00	0.00	0.00

End of hole.

LATITUDE 6° N
DEPARTURE 74 W
ELEVATION

DIP AT COLLAR
BEARING
DEPTH 70.1 m.

0.0 - 7.6 m = 7.6 m (25 ft)

Ag 46.33 g/t.
Pb 2.76%
Zn 5.94%

22.9 - 27.4 = 4.5 m (15 ft)

Ag 47.54 g/t, Pb 2.83%
Zn 6.15%

36.5 - 41.6 = 5.1 m (17.0 ft)

Ag 64.12 g/t.
Pb 3.72%
Zn 6.47%

ASSAY NUMBER	SECTION		CORE LENGTH (m)	ASSAYS		
	From (m)	To (m)		Ag ^{frames} _{frames}	Pb %	Zn %
2062	0.0 ✓	3.0 ✓	3.0	45.26 ✓	2.33 ✓	7.21 ✓
2063	3.0 ✓	6.1 ✓	3.1	41.49 ✓	2.15 ✓	5.81 ✓
2064	6.1 ✓	9.1 ✓	3.0	31.20 ✓	2.05 ✓	4.50 ✓
2065	9.1 ✓	12.1 ✓	3.0	34.29 ✓	2.18 ✓	3.55 ✓
2066	12.1 ✓	13.7 ✓	1.6	27.43 ✓	1.73 ✓	2.45 ✓
2067	13.7 ✓	15.2 ✓	1.5	35.31 ✓	2.55 ✓	2.80 ✓
2068	15.2 ✓	16.0 ✓	0.8	36.34 ✓	2.78 ✓	3.60 ✓
	16.0 ✓	19.8 ✓	3.8	NOT ASSAYED		
2069	19.8 ✓	20.8 ✓	1.0	83.66 ✓	5.26 ✓	8.25 ✓
	20.8 ✓	25.9 ✓	5.1	NOT ASSAYED		
2070	25.9 ✓	28.4 ✓	2.5	38.40 ✓	2.43 ✓	4.75 ✓
	28.4 ✓	29.8 ✓	1.4	NOT ASSAYED		
2071	29.8 ✓	32.0 ✓	2.2	17.14 ✓	1.30 ✓	1.50 ✓
2072	32.0 ✓	35.1 ✓	3.1	24.34 ✓	2.80 ✓	1.18 ✓
2073	35.1 ✓	36.6 ✓	1.5	32.26 ✓	2.68 ✓	3.05 ✓
2074	36.6 ✓	38.1 ✓	1.5	34.29 ✓	1.93 ✓	3.15 ✓
2075	38.1 ✓	39.4 ✓	1.3	29.14 ✓	1.70 ✓	2.30 ✓
2076	39.4 ✓	40.4 ✓	1.0	95.66 ✓	6.01 ✓	9.96 ✓
	40.4 ✓	57.9 ✓	17.5	0.00	0.00	0.00

End of hole.

LATITUDE 10829.438 LN DIP AT COLLAR +60°
 DEPARTURE 7645.418 TW BEARING 30° 12' 15"
 ELEVATION 1148.115 DEPTH 57.9 m (190 ft)

0 - 9.1 m = 9.1 m (30 ft)

Ag. 39.34 g/t, Pb. 2.18%
 Zn 5.84%

19.8 - 20.8 = 1.0 m (3.3 ft) Pb 5.26%

Ag. 83.66 g/t, Zn 8.25%

25.9 - 28.4 = 2.5 m (8.2 ft) Pb 2.43%

Ag. 38.40 g/t, Zn 4.75%

39.4 - 40.4 = 1 m (3.3 ft) Pb. 6.01%

Ag. 95.66 g/t, Zn 9.96%

28.3.76 - 28.3.76

ASSAY NUMBER	SECTION		CORE LENGTH (m)	ASSAYS		
	FROM (m)	TO (m)		Ag ^{grams} _{ounce}	Pb %	Zn %
2077	0.0 ✓	1.8 ✓	1.8	38.40 ✓	2.00 ✓	3.55 ✓
2078	1.8 ✓	3.0 ✓	1.2	50.40 ✓	3.20 ✓	6.46 ✓
2079	3.0 ✓	4.5 ✓	1.5	30.17 ✓	1.70 ✓	3.55 ✓
2080	4.5 ✓	6.0 ✓	1.5	54.51 ✓	2.98 ✓	6.24 ✓
2081	6.0 ✓	7.6 ✓	1.6	50.40 ✓	2.63 ✓	7.80 ✓
2082	7.6 ✓	9.1 ✓	1.5	42.51 ✓	2.30 ✓	5.58 ✓
2083	9.1 ✓	10.6 ✓	1.5	28.46 ✓	1.85 ✓	4.30 ✓
2085	10.6 ✓	12.2 ✓	1.6	30.17 ✓	1.50 ✓	3.43 ✓
2086	12.2 ✓	13.7 ✓	1.5	45.26 ✓	2.68 ✓	4.20 ✓
2087	13.7 ✓	15.2 ✓	1.5	50.40 ✓	2.83 ✓	5.00 ✓
2088	15.2 ✓	16.7 ✓	1.5	40.46 ✓	2.68 ✓	2.90 ✓
2089	16.7 ✓	18.2 ✓	1.5	26.40 ✓	1.55 ✓	2.65 ✓
2090	18.2 ✓	19.8 ✓	1.6	14.06 ✓	0.80 ✓	1.38 ✓
2091	19.8 ✓	21.3 ✓	1.5	4.11 ✓	0.15 ✓	0.25 ✓
	21.3 ✓	28.9 ✓	7.6	NOT ASSAYED		
2092	28.9 ✓	30.0 ✓	1.1	41.49 ✓	2.20 ✓	5.70 ✓
2093	30.0 ✓	33.5 ✓	3.5	55.54 ✓	3.33 ✓	6.60 ✓
2094	33.5 ✓	35.0 ✓	1.5	25.37 ✓	1.55 ✓	2.63 ✓
2095	35.0 ✓	36.5 ✓	1.5	24.34 ✓	1.78 ✓	2.08 ✓
2096	36.5 ✓	38.1 ✓	1.6	40.46 ✓	3.68 ✓	2.20 ✓
2097	38.1 ✓	39.6 ✓	1.5	37.37 ✓	2.30 ✓	4.05 ✓
2098	39.6 ✓	41.1 ✓	1.5	30.17 ✓	1.75 ✓	3.70 ✓
2099	41.1 ✓	42.6 ✓	1.5	36.34 ✓	2.25 ✓	4.30 ✓
2100	42.6 ✓	44.2 ✓	1.6	35.31 ✓	2.28 ✓	4.10 ✓
2101	44.2 ✓	45.7 ✓	1.5	43.94 ✓	6.29 ✓	10.50 ✓
	45.7 ✓	60.9 ✓	15.2	0.00	0.00	0.00

End of hole

LATITUDE 10827.039 LN DIP AT COLLAR +83°
 DEPARTURE 1643.677 T4W BEARING 225° 12' 15"
 ELEVATION 1147.51 DEPTH 60.9 m. (200 ft).

1.8 - 15.2 = 13.4 m (44 ft).

Ag 42.27 g/t. ←
 Pb 2.38 %
 Zn 5.15 %

NOTE Ag change

28.9 - 45.7 = 16.8 m (55 ft)

Ag 43.60 g/t.
 Pb 2.83 %
 Zn 4.78 %

Zinc up

ASSAYS
 NUMBER
 SECTION
 CORE
 FROM (M) TO (M) LENGTH (M)
 Ag. Form
 Pb
 Zn

2102	3.0	6.1	3.1	40.26	1.80	3.10	3.55		
2103	3.0	6.1	3.1	40.26	1.80	3.10	3.55		
2104	6.1	9.1	3.0	34.29	1.65	4.58			
2105	9.1	12.2	3.1	50.40	2.48	4.80			
2106	12.2	15.2	3.0	27.43	1.88	3.15			
2107	15.2	18.3	3.1	29.14	1.35	1.95			
2108	18.3	21.3	3.0	44.23	2.58	5.00			
2109	21.3	24.4	3.1	65.49	4.05	7.75			
2110	24.4	27.4	3.0	45.26	2.65	7.06			
2111	27.4	30.5	3.1	84.69	5.53	10.72			
2112	30.5	32.0	1.5	97.72	6.48	12.34			
2113	32.0	33.5	1.5	87.77	6.28	10.16			
2114	33.5	35.4	1.9	95.66	6.06	12.65			
2115	35.4	37.4	2.0	57.60	3.05	7.27			
2116	40.0	41.1	1.1	71.66	4.75	7.42			
2117	41.1	42.7	1.6	45.26	2.98	4.00			
2118	42.7	45.7	3.0	14.06	0.83	1.63			
2119	45.7	47.2	1.5	18.17	0.63	0.73			
2120	47.2	48.8	1.6	23.31	1.13	1.85			
2121	48.8	50.3	1.5	42.51	2.83	4.65			
2122	50.3	51.8	1.5	74.74	4.95	7.55			
2123	51.8	54.9	3.1	52.46	3.60	7.72			
2124	54.9	57.9	3.0	45.26	2.50	4.65			
2125	62.5	65.5	3.0	40.46	2.68	4.55			
2126	65.5	67.1	1.6	48.34	3.55	6.55			
2127	67.1	68.7	1.6	39.43	2.40	5.64			
2128	68.7	69.7	1.0						
2129	71.2	71.2							
2130	71.2	71.2							

Ag 42.23 g/c (30.34 ft)
 Pb 3.33 g/c
 Zn 5.34 g/c

Ag 52.12 g/c
 Pb 3.33 g/c
 Zn 6.17 g/c

Ag 56.02 g/c (30.34 ft)
 Pb 3.79 g/c
 Zn 5.39 g/c

DDH U. 54

Continued on pages 116 & 117

LATITUDE 10829.438 LN DIP AT CONNAR +60°
 DEPARTURE 1645.418 T4W BEARING 33° 12' 15"
 ELEVATION 1148.115 DEPTH 150.9 m (495 ft)

$$\underline{b.1 - 37.4 = 31.3 \text{ m (102.7 ft)}}$$

Ag 55.62 g/t.

Pb 3.34%

Zn 6.70%

$$\underline{b.1 - 57.9 = 51.8 \text{ m (170 ft)}}$$

Ag 47.74 g/t.

Pb 2.97%

Zn 5.59%

$$\underline{40.0 - 57.9 = 17.9 \text{ m (58.73 ft)}}$$

Ag 40.9 g/t.

Pb 2.55%

Zn 4.45%

$$\underline{b.1 \text{ m} - 71.2 \text{ m} = 65.1 \text{ m (213.6 ft)}}$$

Ag 43.05 g/t.

Pb 2.65%

Zn 5.08%

(E.C.J.)

ASSAY NUMBER	SECTION		CORE LENGTH (m)	ASSAYS			
	From (m)	To (m)		Ag ^{gms} g/t	Pb %	Zn %	
2129	94.1	96.0	1.9	44.23	2.20	3.50	
2130	96.0	97.5	1.5	43.20	2.30	3.80	
2131	97.5	99.1	1.6	35.31	1.85	4.10	
2132	99.1	100.6	1.5	39.43	2.10	3.08	
2133	100.6	102.1	1.5	48.34	2.55	4.10	6.0 m (19.7 ft)
2134	102.1	103.5	1.4	96.69	4.28	10.82	Ag 80.06 g/t.
2135	103.5	105.0	1.5	83.66	3.75	7.72	Pb 3.73%
2136	105.0	106.6	1.6	91.89	4.35	10.67	Zn 8.33%
2137	106.6	109.3	2.7	25.37	1.25	4.00	
	109.3	115.3	6.0	NOT ASSAYED			
2138	115.3	116.9	1.6	26.34	1.90	5.40	
	116.9	150.9	34.0	0.00	0.00	0.00	

End of hole.

(E.C.J.)

DDH. U-55

Assay No.	Section		Core Length	Assays.		
	From	To		Ag g/t	Pb %	Zn %
	0.0	36.4	36.4	0.00	0.00	0.00

End of hole

$$94.1 - 109.3 = 15.2 \text{ m (50 ft)}$$

Ag 53.51 g/t

Pb 2.60%

Zn 5.54%

$$115.3 - 116.9 = 1.6 \text{ m (5.25 ft)}$$

Ag 36.34 g/t; Pb 1.90% Zn 5.40%

DDH U. 55' ^{65'}
 NAT. 10826.027 DEP 7643.137
 DIP +27° BEARING 233° 40' 23"
 ELEVATION 1145.06 LENGTH 36.4m.
NO ASSAYS.

ASSAY NUMBER	SECTION		CORE LENGTH (M)	ASSAYS		
	FROM (M)	TO (M)		Ag ^{from stone}	Pb %	Zn %
	0.0	1.8	1.8	0.00	0.00	0.00
2139	1.8	3.0	1.2	21.26	1.38	1.73
2140	3.0	4.5	1.5	19.20	0.90	1.85
2141	4.5	6.1	1.6	10.97	0.40	1.90
2142	6.1	7.6	1.5	15.09	0.75	2.98
2143	7.6	9.1	1.5	31.20	1.75	4.55
2144	9.1	10.6	1.5	30.17	1.33	3.30
2145	10.6	12.1	1.5	26.40	1.35	3.53
2146	12.1	13.7	1.6	30.17	1.38	4.20
2147	13.7	15.2	1.5	29.14	1.48	3.73
2148	15.2	16.7	1.5	25.37	1.15	2.68
2149	16.7	18.2	1.5	46.29	2.43	4.85
2150	18.2	19.8	1.6	32.23	1.78	3.53
2151	19.8	21.3	1.5	32.23	3.23	3.75
	21.3	45.0	23.7	NOT ASSAYED		
2152	45.0	47.2	2.2	37.37	2.30	3.60
2153	47.2	48.7	1.5	20.23	0.80	1.55
2154	48.7	50.2	1.5	15.09	0.90	1.28
2155	50.2	51.8	1.6	18.17	1.62	0.88
2156	51.8	53.3	1.5	49.37	4.25	4.35
2157	53.3	54.8	1.5	41.49	3.60	7.77
2158	54.8	56.3	1.5	37.37	3.00	5.84
	56.3	61.0	4.7	0.00	0.00	0.00

End of hole

LATITUDE 10 525.996 6N DIP AT COLLAR +28°
 DEPARTURE 7643.189 74W BEARING 223° 41' 55"
 ELEVATION 1146.126 DEPTH 61M (200 ft)

16.7 - 21.3 = 4.6m (15 ft)
 Ag 36.81 g/t. Pb 2.46
 Zn 4.03

low

51.8 - 56.3 = 4.5m (14.75 ft)
 Ag 42.74 g/t. Pb 3.61%
 Zn 5.99%

ASSAY NUMBER	SECTION		CORE LENGTH (M)	ASSAYS		
	FROM (M)	TO (M)		Ag ^{grams} / _{ounce}	Pb %	Zn %
2159	0.0	1.5	1.5	39.43	1.70	4.85
2160	3.0	3.0	1.5	43.54	2.40	3.85
2161	3.0 4.5	4.5	1.5	14.06	0.70	2.15
2162	4.5 6.0	6.0	1.5	29.14	1.55	3.70
2163	6.0 7.6	7.6	1.6	23.31	1.33	3.58
2164	7.6 9.1	9.1	1.5	26.40	1.33	4.20
2165	9.1 13.7	13.7	4.6	29.14	1.98	4.03
2166	13.7 15.2	15.2	1.5	20.23	1.25	3.78
2167	15.2	16.7	1.5	40.46	2.40	5.70
2168	16.7	18.2	1.5	35.31	2.10	1.82
2169	18.2	19.8	1.6	42.51	2.68	6.15
2170	19.8	21.3	1.5	36.34	2.33	5.00
2171	21.3	22.8	1.5	38.40	2.75	4.70
2172	22.8	24.3	1.5	29.14	2.23	4.15
2173	24.3	25.9	1.6	15.09	1.15	3.18
	25.9	27.4	1.5	NOT ASSAYED		
2174	27.4	28.9	1.5	50.40	3.20	5.60
2175	28.9	30.0	1.1	19.20	1.35	3.40
2176	30.0	32.0	2.0	45.26	3.45	5.84
2177	32.0	33.5	1.5	24.34	1.73	3.98
	33.5	45.7	12.2	NOT ASSAYED		
2178	45.7	47.2	1.5	8.23	0.50	1.05
2179	47.2	48.7	1.5	13.03	0.78	0.55
	48.7	50.3	1.6	NOT ASSAYED		
2180	50.3	51.8	1.5	9.94	0.53	0.50
2181	51.8	53.3	1.5	13.03	0.63	0.55

End of hole

LATITUDE 10329.897 (6N) DIP AT COLLAR + 28°
 DEPARTURE 1643.083 (14W) BEARING 220° 16' 53"
 ELEVATION 1143.826 LENGTH 53.3m (175 ft)

0.0 - 33.5m (110 ft).
 Ag 30.26 g/t.
 Pb 1.93% } combined 6.18%
 Zn 4.25%

15.2 - 24.3 = 9.1m (30 ft)
 Ag 37.09 g/t
 Pb 2.46%
 Zn 5.59%

15.2 - 32.0 = 16.8m (55 ft).
 Ag 32.67 g/t.
 Pb 2.23% } combined 6.94%
 Zn 4.71%

how

E.C.J.

S. 4. 76. 6. 4. 76

ASSAY NUMBER	SECTION		CORE LENGTH (M)	ASSAYS		
	FROM (M)	TO (M)		Ag. ^{Trace} Trace	Pb %	Zn %
2182	0.0	1.5	1.5	50.40	3.45	3.65
2183	1.5	3.0	1.5	36.34	2.38	2.60
2184	3.0	4.5	1.5	85.12	7.42	11.57
2185	4.5	6.0	1.5	104.92	7.10	9.41
2186	6.0	7.6	1.6	155.32	7.30	12.68
2187	7.6	9.1	1.5	111.09	8.33	13.80
2188	9.1	10.6	1.5	16.11	0.85	1.25
2189	10.6	12.1	1.5	31.20	1.83	2.70
2190	12.1	13.7	1.6	40.46	2.23	4.10
2191	13.7	15.2	1.5	77.83	4.98	10.85
2192	15.2 15.2	16.7	1.5	98.74	6.62	15.67
2193	16.7	19.0	2.3	90.86	6.12	15.12
	19.0	86.8	67.8	NOT ASSAYED		
2194	86.8	88.2	1.5	57.60	5.05	2.44
2195	88.3	89.9	1.6	60.34	5.00	3.05
2196	89.9	91.4	1.5	20.23	0.33	0.13
2197	91.4	93.0	1.6	17.14	0.48	0.33
2198	93.0	94.5	1.5	80.57	5.15	5.05
2199	94.5	96.0	1.5	49.37	2.03	0.85
2200	96.0	97.5	1.5	88.00	5.00	1.83
2201	97.5	99.0	1.5	41.49	2.53	2.75
2202	99.0	100.5	1.5	47.31	3.50	4.10
	100.5	106.6	6.1	0.00	0.00	0.00

End of hole

LATITUDE 32 10797.873
 DEPARTURE 16W 7534.521
 ELEVATION 1136.292

DIP AT COLLAR +1° 40'
 BEARING. 223° 41' 31"
 DEPTH 106.6 m (350 ft)

0.0 - 9.1 m = 9.1 m (30 ft)

Ag 105.64 g/t.

Pb 6.01%

Zn 9.29%

0 - 19.0 m = 19.0 m (62.3 ft)

Ag 82.68 g/t.

Pb 4.93%

Zn 7.62%

12.1 - 19.0 m = 6.9 m (22.64 ft)

Ag 78.05 g/t.

Pb 5.08%

Zn 7.77%

86.8 - 89.9 = 3.1 m (10.2 ft) Ag 59.01 g/t.

Pb 5.02% Zn 2.75%

86.8 - 100.5 = 13.7 m (45 ft)

Ag 51.24 g/t.

Pb 3.22%

Zn 2.27%

LOW

93.0 - 94.5 = 1.5 m (4.92 ft) Ag 80.57 g/t.

Pb 5.15% Zn 5.05%

96.0 - 97.5 = 1.5 m (4.92 ft) Ag 88.0 g/t.

Pb 5.00% Zn 1.83%

99.0 - 100.5 = 1.5 m (4.92 ft) Ag 47.31 g/t.

Pb 3.50% Zn 4.10%



ASSAY

SECTION

CORRE

ASSAYS

NUMBER

From (m) to (m) length (m)

Ag per cent

Pb

Sn

2203

0.0

1.5

1.5

55.54

3.8

8.22

2204

1.5

3.0

1.5

66.51

4.43

10.12

2205

3.0

4.5

1.5

40.46

2.70

4.60

2206

4.5

6.1

1.6

69.60

4.98

9.08

2207

6.1

7.6

1.5

60.34

4.25

8.60

2208

7.6

9.1

1.5

76.80

5.70

10.65

2209

9.1

10.6

1.5

137.14

8.73

17.15

2210

10.6

12.1

1.5

163.54

11.26

19.08

2211

12.1

13.6

1.5

149.14

9.63

15.98

2212

13.6

15.1

1.5

153.26

10.33

18.33

2213

15.1

16.5

1.4

197.83

13.29

18.52

2214

16.5

18.0

1.5

76.80

5.49

6.90

2215

18.0

19.5

1.5

163.54

13.22

15.37

2216

19.5

21.2

1.5

153.26

11.09

18.22

2217

21.0

22.5

1.5

121.03

7.20

9.84

2218

22.5

24.0

1.5

113.14

7.25

10.55

2219

24.0

25.5

1.5

129.26

8.00

10.96

2220

25.5

27.0

1.5

114.56

7.15

10.20

2221

27.0

28.5

1.5

123.09

7.20

10.80

2222

28.5

30.0

1.5

123.09

7.00

9.90

2223

30.0

31.5

1.5

139.20

9.20

12.28

2224

31.5

33.0

1.5

111.09

7.60

10.15

2225

33.0

34.5

1.5

151.20

10.95

13.95

2226

34.5

36.0

1.5

143.32

9.50

13.39

2227

36.0

37.5

1.5

104.92

7.20

10.00

2228

37.5

39.0

1.5

100.80

7.10

10.45

2229

39.0

40.5

1.5

96.69

7.70

10.96

2230

40.5

42.0

2.1

109.03

6.80

9.79

2231

42.0

44.2

1.6

104.92

6.90

10.60

2232

44.2

47.2

1.5

127.20

6.92

12.53

2233

47.2

47.2

1.5

163.54

8.85

12.29

2234

47.2

48.7

1.5

139.20

9.08

17.70

2235

48.7

50.3

1.6

121.03

8.53

13.55

2236

50.3

51.8

1.5

25.37

1.28

0.43

2237

51.8

53.3

1.5

12.00

0.28

0.53

2238

53.3

54.8

1.5

98.74

5.22

8.73

2239

102.1

102.1

47.3

NOT ASSAYED

2239

103.6

103.6

1.5

27.43

2.00

2.38

2240

103.6

105.1

1.5

32.23

8.40

2.60

2241

105.1

106.6

1.5

8.23

0.23

0.54

2242

106.6

108.2

1.6

6.17

0.10

0.25

2243

108.2

109.7

1.5

8.91

0.38

0.45

2244

109.7

110.5

0.8

19.20

1.38

1.30

End of H66

110.5

127.2

16.7

0.00

0.00

0.00

7.4.76 . 9.4.76

LATITUDE 3N 10798.160

DIP AT CORNER -15°

DEPARTURE 76W 1534.893

BEARING $227^{\circ} 06' 12''$

ELEVATION 1135.444

DEPTH 127.2 m (417 ft).

0.0 - 54.8 m = 54.8 m (180 ft)

Ag 194.5 g/t.

Pb 7.88%

Zn 11.35%

10.4.76 - 11.4.76

ASSAY NUMBER	SECTION		CORE LENGTH (M)	ASSAYS		
	FROM (M)	TO (M)		Ag ^{Francis} Francis	Pb%	Zn%
2247	0.0	1.5	1.5	37.37	3.20	3.75
2248	1.5	3.0	1.5	34.29	3.90	4.95
2249	3.0	4.5	1.5	29.14	2.73	4.70
2250	4.5	6.1	1.6	31.20	3.03	2.85
2251	6.1	7.6	1.5	44.23	4.08	3.70
2252	7.6	9.1	1.5	27.43	2.05	3.75
2253	9.1	10.6	1.5	7.20	0.43	1.58
2254	10.6	12.2	1.6	40.46	3.40	4.05
2255	12.2	13.7	1.5	23.31	1.75	1.75
2256	13.7	15.2	1.5	17.14	1.10	0.88
2257	15.2	16.7	1.5	23.31	1.50	1.48
2258	16.7	18.2	1.5	28.46	1.63	2.13
2259	18.2	19.8	1.6	20.23	0.88	1.25
2260	19.8	21.3	1.5	24.34	1.25	1.50
2261	21.3	22.8	1.5	20.23	1.05	1.35
2262	22.8	24.4	1.6	35.31	2.05	3.75
2263	24.4	26.0	1.6	32.23	2.08	2.05
2264	26.0	27.4	1.4	47.31	3.33	4.40
2265	27.4	28.9	1.5	14.06	0.35	1.40
2266	28.9	30.0	1.1	68.57	4.58	7.21
2267	30.0	32.0	2.0	63.43	4.55	4.45
2268	32.0	33.5	1.5	89.83	6.10	8.46
2269	33.5	35.0	1.5	70.62	4.08	5.55
	35.0	42.6	7.6	NOT ASSAYED		
2270	42.6	44.1	1.5	55.54	3.85	4.90
	44.1	56.3	12.2	NOT ASSAYED		
2271	56.3	57.9	1.6	39.43	1.28	2.10
2272	57.9	59.4	1.5	9.94	0.45	0.80
2273	59.4	61.0	1.6	114.86	7.20	13.64
2274	61.0	62.5	1.5	74.74	4.88	8.49
	62.5	105.1	42.6	NOT ASSAYED		
2275	105.1	106.6	1.5	90.86	5.80	8.90
2276	106.6	108.2	1.6	51.43	3.05	5.00
2277	108.2	109.7	1.5	76.80	4.53	6.85
2278	109.7	111.2	1.5	26.40	1.13	2.78
2279	111.2	112.7	1.5	48.34	2.80	4.20
	112.7	122.0	9.3	0.00	0.00	0.00

End of hole.

LATITUDE 3N 10799.368

DIP AT COLLAR

DEPARTURE 76W. 7535.886

BEARING

ELEVATION 1134.969.

DEPTH 122 m (400ft).

0.0 - 4.5 m = 4.5 m (14.8 ft)

Ag. 33.6 g/t, Pb 3.28%

Zn. 4.47%

0 - 7.6 m = 7.6 m (25.0 ft)

Ag 35.19 g/t.

Pb 3.38%

Zn 3.34%

LOW

6.1 - 7.6 m = 1.5 m (4.9 ft) Ag. 44.23 g/t.

Pb 6.12% Zn 3.70%

10.6 - 12.2 m = 1.6 m (5.25 ft) Ag. 40.46 g/t.

Pb. 3.40% Zn 4.05%

26.0 - 35.0 = 9.0 m (29.5 ft)

Ag 58.92 g/t.

Pb 3.84%

Zn. 5.06%

42.6 - 44.1 m = 1.5 m (4.9 ft) Ag 55.54 g/t.

Pb. 3.85% Zn 4.90%

59.4 - 62.5 m = 3.1 m (10.2 ft) Ag. 99.45 g/t.

Pb 6.08% Zn 11.15%

105.1 - 112.7 m = 7.6 m (24.9 ft)

Ag 58.67 g/t.

Pb 3.46%

Zn. 5.54%

ASSAY NUMBER SECTION CORE ASSAYS

From (m) / to (m) LENGTH (m) *Ag. tests* *bx* *32*

8.08 / 4.88 / 80.57 / 1.5 / 1.5

5.55 / 3.78 / 38.40 / 1.5 / 1.5

4.10 / 2.83 / 30.17 / 1.5 / 1.5

4.45 / 3.40 / 38.40 / 1.6 / 1.6

5.25 / 4.13 / 53.49 / 1.5 / 1.5

5.35 / 4.08 / 70.63 / 1.5 / 1.5

1.10 / 0.83 / 26.40 / 1.5 / 1.5

0.45 / 0.10 / 12.00 / 1.5 / 1.5

0.95 / 0.90 / 38.40 / 1.6 / 1.6

1.23 / 0.75 / 22.29 / 1.5 / 1.5

3.55 / 2.04 / 43.54 / 1.5 / 1.5

0.63 / 0.58 / 26.40 / 1.5 / 1.5

18.2 / 19.8 / 12.00 / 1.5 / 1.5

19.8 / 21.3 / 16.11 / 1.6 / 1.6

22.8 / 21.3 / 8.91 / 1.5 / 1.5

0.17 / 0.12 / 9.94 / 1.5 / 1.5

7.16 / 7.17 / 109.03 / 1.6 / 1.6

8.41 / 11.16 / 161.49 / 1.5 / 1.5

5.10 / 9.63 / 147.09 / 1.5 / 1.5

0.51 / 1.23 / 31.20 / 1.1 / 1.1

8.79 / 7.27 / 90.86 / 2.0 / 2.0

4.00 / 2.83 / 50.40 / 1.5 / 1.5

33.5 / 54.8 / 21.3 / 3.1 / 3.1

54.8 / 56.3 / 59.4 / 1.5 / 1.5

2.40 / 1.75 / 30.17 / 1.5 / 1.5

59.4 / 60.9 / 94.63 / 1.5 / 1.5

60.9 / 86.8 / 25.9 / 15.2 / 15.2

86.8 / 88.3 / 27.43 / 1.5 / 1.5

89.9 / 89.9 / 35.31 / 1.6 / 1.6

91.4 / 91.4 / 40.56 / 1.5 / 1.5

92.9 / 92.9 / 24.34 / 1.5 / 1.5

94.4 / 94.4 / 8.91 / 1.5 / 1.5

94.4 / 96.0 / 8.23 / 1.6 / 1.6

112.7 / 114.3 / 129.26 / 1.6 / 1.6

114.3 / 115.8 / 72.69 / 1.5 / 1.5

115.8 / 120.3 / 4.5 / 1.5 / 1.5

111.2 / 112.7 / 10.63 / 1.5 / 1.5

112.7 / 114.3 / 129.26 / 1.6 / 1.6

114.3 / 115.8 / 72.69 / 1.5 / 1.5

115.8 / 120.3 / 4.5 / 1.5 / 1.5

End of log.

LATITUDE 3N 10799.082

DIP AT COLLAR

DEPARTURE 76W 7535.677

BEARING

ELEVATION 1135.001

DEPTH 120.3 m (395 ft)

00-9.1 m = 9.1 m (29.86 ft)

Ag 51.79 g/t.

Pb 3.85%

Zn 5.45%

24.3-33.5 m = 9.2 m (30.18 ft)

Ag 100.97 g/t.

Pb 6.83%

Zn 6.07%

59.4-60.9 m = 1.5 m (4.9 ft) Ag 94.63 g/t.

Pb 5.80% Zn 9.41%

112.2-115.8 m = 3.6 m (11.8 ft)

Ag 91.69 g/t.

Pb 5.81% Zn 11.35%

14.4.76 - 15.4.76

ASSAY

SECTION

CORE

ASSAYS

NUMBER	From (m)	To (m)	LENGTH (m)	Ag. from	Pb	Zn
2313	0.0	1.5	1.5	106.97	7.97	9.95
2314	1.5	3.0	1.5	96.69	6.40	5.60
2315	3.0	4.5	1.5	65.49	4.50	4.35
2316	4.5	6.0	1.5	63.43	3.70	4.00
2317	6.0	7.1	1.1	130.97	6.72	9.23
2318	7.1	9.1	2.0	187.14	6.00	8.00
2319	9.1	10.6	1.5	101.83	4.63	7.26
2320	10.6	12.1	1.5	116.92	6.90	12.57
2321	12.1	13.7	1.6	76.80	5.25	9.58

End of hole

LATITUDE 3N 10798.093
 DEPARTURE 76M 7534.797
 ELEVATION 1135.596

DIP AT CORNER - 21°
 BEARING 222° 17' 48"
 DEPTH 109.7 m (360 ft)

0 - 13.7 m = 13.7 m (44.95 ft)

Ag 99.87 g/t
 Pb 5.69%
 Zn 7.74%

89.9 - 97.5 m = 7.6 m (24.9 ft)

Ag 101.69 g/t
 Pb 5.25%
 Zn 7.91%

13.7 89.9 76.2 NOT ASSAYED

2322	89.9	91.4	1.5	85.72	4.30	6.55
2323	91.4	92.9	1.5	109.03	5.85	8.79
2324	92.9	94.4	1.5	118.97	6.60	8.94
2325	94.4	96.0	1.6	116.92	5.50	9.19
2326	96.0	97.5	1.5	76.80	4.00	5.95
2327	97.5	109.7	12.2	0.00	0.00	0.00

E.C.J.

15.4.76 - 17.4.76

ASSAY NUMBER	SECTION		CORE LENGTH (M)	ASSAYS		
	FROM (M)	TO (M)		Ag ^{grams} / _{per tonne}	Pb %	Zn %
2327	0.0 ✓	1.5 ✓	1.5	96.69 ✓	8.50 ✓	14.87 ✓
2328	1.5 ✓	3.0 ✓	1.5	88.80 ✓	7.60 ✓	10.27 ✓
2329	3.0 ✓	4.5 ✓	1.5	135.09 ✓	5.97 ✓	8.48 ✓
2330	4.5 ✓	6.0 ✓	1.5	121.03 ✓	5.79 ✓	10.58 ✓
2331	6.0 ✓	7.6 ✓	1.6	104.92 ✓	6.25 ✓	11.70 ✓
2332	7.6 ✓	9.1 ✓	1.5	100.80 ✓	7.77 ✓	12.73 ✓
2333	9.1 ✓	10.6 ✓	1.5	80.57 ✓	6.65 ✓	20.48 ✓
2334	10.6 ✓	12.1 ✓	1.5	48.34 ✓	3.30 ✓	14.21 ✓
12.1 - 39.6 ✓ 27.5				NOT ASSAYED		
2335	39.6 ✓	41.1 ✓	1.5	70.63 ✓	7.92 ✓	4.10 ✓
2336	41.1 ✓	42.6 ✓	1.5	68.57 ✓	7.10 ✓	3.90 ✓
42.6 - 56.3 ✓ 13.7				NOT ASSAYED		
2337	56.3 ✓	57.9 ✓	1.6	54.51 ✓	3.88 ✓	4.35 ✓
2338	57.9 ✓	59.4 ✓	1.5	47.31 ✓	3.15 ✓	2.60 ✓
2339	59.4 ✓	60.9 ✓	1.5	71.66 ✓	4.70 ✓	6.42 ✓
2340	60.9 ✓	62.4 ✓	1.5	113.14 ✓	7.32 ✓	8.18 ✓
2341	62.4 ✓	64.0 ✓	1.6	221.83 ✓	15.00 ✓	12.57 ✓
64.0 - 106.6 ✓ 42.6				0.00 0.00 0.00		

End of hole

1281

LATITUDE 3N 10798.012
 DEPARTURE 16W. 7534.767
 ELEVATION 1137.448
 DIP AT COLLAR +32° 30'
 BEARING 222° 14' 29"
 DEPTH 106.6 m (350 ft)

0.0 - 12.1 m = 12.1 m (39.7 ft)

Ag 82.08 g/t
 Pb 6.47 %
 Zn 12.9 %

39.6 - 42.6 = 3.0 m (9.84 ft) Ag 69.6 g/t

Pb 7.51 %
 Zn 4.0 %

56.3 - 64.0 = 7.7 m

Ag 102.73 g/t
 Pb 6.68 %
 Zn 6.87 %

17.4.76 - 18.4.76

ASSAY NUMBER	SECTION		CORE LENGTH (M)	ASSAYS		
	FROM (M)	TO (M)		Ag ^{fraction} per tonne	Pb %	Zn %
2342	0.0	1.5	1.5	54.51	4.23	8.23
2343	1.5	3.0	1.5	109.03	9.00	13.85
2344	3.0	4.5	1.5	114.86	6.40	9.41
2345	4.5	6.0	1.5	153.26	7.05	9.92
2346	6.0	7.6	1.6	129.26	6.45	9.77
2347	7.6	9.1	1.5	137.14	7.40	11.75
2348	9.1	10.6	1.5	147.09	9.56	15.49
2349	10.6	12.1	1.5	86.74	5.30	4.60
2350	12.1	13.7	1.6	90.86	6.07	8.33
2351	13.7	15.2	1.5	41.49	2.68	5.40
2352	15.2	16.7	1.5	118.97	5.65	10.10
	16.7	38.1	21.4	NOT ASSAYED		
2353	38.1	39.6	1.5	100.8	9.41	7.26
2354	39.6	41.1	1.5	50.4	4.78	4.70
	41.1	57.9	16.8	0.00	0.00	0.00

End of hole.

LATITUDE 3N 10799.507
 DEPARTURE 76W 7537.073
 ELEVATION 1138.802

DIP AT COLLAR + 63° 50'
 BEARING 221° 23' 19"
 DEPTH 57.9 m (190 ft)

0.0 - 16.7 m = 16.7 m (54.8 ft)

Ag 107.59 g/t.
 Pb 6.32%
 Zn 9.71%

38.1 - 41.1 m = 3 m (9.84 ft) Ag 75.6 g/t.
 Pb 7.17% Zn 5.98%

E.C.J.

18.4.76 - 19.4.76

ASSAY NUMBER	SECTION		CORE LENGTH (m)	ASSAYS		
	FROM (m)	TO (m)		Ag ^{from} from	Pb %	Zn %
2355	0.0 ✓	1.5 ✓	1.5	68.43 ✓	4.23 ✓	8.84 ✓
2356	1.5 ✓	3.0 ✓	1.5	91.89 ✓	7.69 ✓	11.06 ✓
2357	3.0 ✓	4.5 ✓	1.5	146.06 ✓	8.33 ✓	12.65 ✓
2358	4.5 ✓	6.0 ✓	1.5	121.03 ✓	6.49 ✓	8.98 ✓
2359	6.0 ✓	7.6 ✓	1.6	111.09 ✓	6.10 ✓	10.05 ✓
2360	7.6 ✓	9.1 ✓	1.5	161.49 ✓	8.55 ✓	14.59 ✓
2361	9.1 ✓	10.6 ✓	1.5	169.37 ✓	8.65 ✓	14.69 ✓
2362	10.6 ✓	12.1 ✓	1.5	117.94 ✓	8.43 ✓	14.38 ✓
2363	12.1 ✓	13.7 ✓	1.6	87.77 ✓	4.85 ✓	12.80 ✓
2364	13.7 ✓	15.2 ✓	1.5	79.20 ✓	4.58 ✓	10.20 ✓
2365	15.2 ✓	16.7 ✓	1.5	75.77 ✓	4.38 ✓	4.70 ✓
2366	16.7 ✓	18.2 ✓	1.5	161.49 ✓	10.55 ✓	16.57 ✓
2367	18.2 ✓	19.8 ✓	1.6	126.17 ✓	8.63 ✓	12.13 ✓
2368	19.8 ✓	21.3 ✓	1.5	14.06 ✓	1.30 ✓	2.23 ✓
	21.3	42.6	21.3	NOT	ASSAYED	
2369	42.6 ✓	44.1 ✓	1.5	45.26 ✓	3.45 ✓	2.95 ✓
2370	44.1 ✓	45.7 ✓	1.6	179.66 ✓	14.33 ✓	11.98 ✓
2371	45.7 ✓	47.2 ✓	1.5	188.57 ✓	15.28 ✓	8.98 ✓
2372	47.2 ✓	48.7 ✓	1.5	157.37 ✓	15.53 ✓	11.47 ✓
2373	48.7 ✓	50.2 ✓	1.5	70.63 ✓	4.95 ✓	3.70 ✓
	50.2 ✓	59.4 ✓	9.2	0.00	0.00	0.00

End of hole

LATITUDE 10799.568
 DEPARTURE 7535.976
 ELEVATION 1139.029

DIP AT COLLAR. +88° 09'
 BEARING 339° 16' 28"
 DEPTH 59.4 m (195 ft)

0.0 - 19.8 = 19.8 m (65 ft)

Ag 103.41 g/t.
 Pb 7.03%
 Zn 11.66%

42.6 - 50.2 = 7.6 m (25 ft)

44.1 - 50.2 = 6.1 m (20.0 ft)

Ag 149.45 g/t
 Pb 11.81%
 Zn 9.08%

Ag 128.9 g/t.
 Pb 10.16%
 Zn 7.87%



DDH U. 64

19.4.76 - 20.4.76

ASSAY SECTION CORE ASSAYS

NUMBER From (m) to (m) Length (m) Ag. Ferr. PbZn

0.0 1.5 3.0 108.00 8.17 15.09 10.89 10.89 8.59 10.88

2374 0.0 1.5 143.32 10.12 13.52

2375 1.5 3.0 108.00 8.17 15.09

2376 3.0 4.5 84.69 5.51 10.89

2377 4.5 6.0 50.42 4.28 8.59

2378 6.0 7.6 77.83 7.00 10.88

2379 7.6 9.1 129.26 6.80 9.44

2380 9.1 10.6 126.17 5.90 9.54

2381 10.6 12.1 94.63 5.20 8.95

2382 12.1 13.7 73.71 3.58 8.06

2383 13.7 15.2 89.83 5.44 8.93

2384 15.2 16.7 64.46 3.55 6.17

2385 16.7 18.2 56.57 3.88 4.22

2386 18.2 19.8 34.29 2.75 1.40

2387 19.8 21.3 101.83 8.77 13.21

2388 21.3 22.8 111.09 7.59 14.69

2389 22.8 24.3 98.74 7.25 14.25

2390 24.3 25.9 69.60 5.59 21.24

2391 25.9 27.2 56.57 4.68 3.10

2392 27.2 28.6 81.26 1.33 1.05

2393 28.6 29.9 19.20 1.43 1.13

2394 29.9 31.2 14.06 1.20 0.98

2395 31.2 32.5 30.17 2.35 1.68

2396 32.5 33.8 45.86 2.53 0.53

2397 33.8 35.1 60.34 3.98 4.85

2398 35.1 36.4 37.37 2.08 1.55

2399 36.4 37.7 111.09 6.70 5.64

2400 37.7 39.0 84.69 5.80 7.10

2401 39.0 40.3 80.57 6.55 8.07

2402 40.3 41.6 138.17 9.33 10.08

2403 41.6 42.9 37.37 2.70 1.55

2404 42.9 44.2 26.40 1.80 1.00

2405 44.2 45.5 72.69 4.18 3.45

2406 45.5 46.8 54.51 4.50 3.80

2407 46.8 48.1 73.71 5.75 7.45

2408 48.1 49.4 100.80 6.10 8.78

2409 49.4 50.7 98.74 6.80 7.72

2410 50.7 52.0 35.31 2.48 2.35

2411 52.0 53.3 79.54 5.25 6.21

2412 53.3 54.6 100.80 5.90 8.02

2413 54.6 55.9 105.94 6.20 8.88

End of log

DEPA

FILE

0.0

23.2

73

LATITUDE 3N 10797.703

DIP AT COLLAR +23°

DEPARTURE 16W, 7536.365

BEARING 176° 26' 01"

ELEVATION 1136.900

DEPTH 99.0 m (325 ft)

0.0 - 25.9 m = 25.9 m (85 ft)

Ag 88.70 g/t.

Pb 5.94%

Zn 10.72%

39.2 - 41.1 = 1.9 m (6.23 ft) Ag 56.51 g/t. Pb 4.68% Zn 3.10%73.1 - 99.0 = 25.9 m (85 ft)

Ag 76.06 g/t.

Pb 5.05%

Zn 5.71%

E.C.I.

26.4.76 - 26.4.76

ASSAY NUMBER	SECTION		CORE LENGTH (m)	ASSAYS		
	From (m)	To (m)		Ag ^{from} _{tonne}	Pb %	Zn %
2414	0.0	1.5	1.5	20.23	1.33	0.95
2415	1.5	3.0	1.5	36.34	3.23	2.50
2416	3.0	4.5	1.5	14.00	0.95	0.40
2417	4.5	6.0	1.5	40.46	3.93	4.40
2418	6.0	7.6	1.6	33.26	2.68	4.95
2419	7.6	9.1	1.5	42.51	3.30	3.90
2420	9.1	10.6	1.5	32.23	2.78	4.00
2421	10.6	12.1	1.5	18.17	0.79	2.05
2422	12.1	13.7	1.6	15.09	0.78	1.70
2423	13.7	15.2	1.5	39.43	2.30	2.75
2424	15.2	16.7	1.5	42.51	2.68	5.82
2425	16.7	18.2	1.5	67.54	4.93	10.11
2426	18.2	19.8	1.6	128.23	9.45	13.79
2427	19.8	21.3	1.5	100.80	10.51	13.81
2428	21.3	22.8	1.5	114.17	8.20	12.82
2429	22.8	24.3	1.5	41.49	2.23	5.00
2430	24.3	25.9	1.6	65.49	3.43	8.12
2431	25.9	27.4	1.5	100.80	6.12	13.01
2432	27.4	28.9	1.5	36.34	2.63	17.20
2433	28.9	30.4	1.5	58.63	5.40	21.54
2434	30.4	32.0	1.6	67.54	5.50	22.72
2435	32.0	33.5	1.5	80.57	5.95	22.18
2436	33.5	35.0	1.5	121.03	5.15	17.52
2437	35.0	36.5	1.5	50.40	2.50	5.00
	36.5	76.2	39.7	0.00	0.00	0.00

End of hole

LATITUDE 3N 10842.752
 DEPARTURE 78W 7493.677
 ELEVATION 1126.585

DIP AT COLLAR +01°
 BEARING 225° 28' 17"
 DEPTH 76.2 m (250 ft)

4.5 - 10.6 = 6.1 m (20 ft)

Ag 37.05 g/t
 Pb 3.16 %
 Zn 4.32 %

4.5 - 36.5 = 32 m (105 ft)

Ag 58.62 g/t
 Pb 3.74 %
 Zn 9.29 %

13.7 - 36.5 = 22.8 m (75 ft)

Ag 70.11 g/t
 Pb 5.14 %
 Zn 12.79 %

(E.C.J.)

26.4.76 - 27.4.76

ASSAY NUMBER	SECTION		CORE LENGTH	ASSAYS		
	FROM (m)	TO (m)		Ag ^{gms} / _{ton}	Pb %	Zn %
2438	0.0 ✓	1.5 ✓	1.5	12.00 ✓	0.58 ✓	0.53 ✓
2439	1.5 ✓	3.0 ✓	1.5	20.23 ✓	1.00 ✓	0.53 ✓
2440	3.0 ✓	4.5 ✓	1.5	28.46 ✓	2.28 ✓	1.23 ✓
2441	4.5 ✓	6.0 ✓	1.5	26.40 ✓	2.35 ✓	1.00 ✓
2442	6.0 ✓	7.6 ✓	1.6	33.26 ✓	3.05 ✓	4.95 ✓
2443	7.6 ✓	9.1 ✓	1.5	32.23 ✓	2.13 ✓	4.73 ✓
2444	9.1 ✓	10.6 ✓	1.5	50.50 ✓	3.55 ✓	5.83 ✓
2445	10.6 ✓	12.1 ✓	1.5	113.14 ✓	8.20 ✓	14.72 ✓
2446	12.1 ✓	13.7 ✓	1.6	166.29 ✓	8.93 ✓	15.43 ✓
2447	13.7 ✓	15.2 ✓	1.5	133.03 ✓	10.48 ✓	19.44 ✓
2448	15.2 ✓	16.7 ✓	1.5	132.00 ✓	7.92 ✓	14.84 ✓
2449	16.7 ✓	18.2 ✓	1.5	74.74 ✓	3.78 ✓	9.33 ✓
2450	18.2 ✓	19.8 ✓	1.6	105.94 ✓	6.77 ✓	13.09 ✓
2451	19.8 ✓	21.3 ✓	1.5	49.37 ✓	3.18 ✓	3.10 ✓
2452	21.3 ✓	22.8 ✓	1.5	52.46 ✓	3.20 ✓	4.35 ✓
	22.8 ✓	53.3 ✓	30.5	0.00	0.00	0.00

End of hole

LATITUDE 3N 10841.812
 DEPARTURE 78W 7493.520
 ELEVATION 1127.786

DIP AT COLLAR +33°
 BEARING 223° 26' 44"
 DEPTH 53.3 m (175 ft)

$6.0 - 22.8 = 16.8 \text{ m (14.8 ft)}$

Ag 86.0 g/t.

Pb 5.66%

Zn 10.00%

E.C.J.

27.4.76 - 27.4.76

ASSAY NUMBER	SECTION		CORE LENGTH	ASSAYS		
	FROM (M)	TO (M)		Ag ^{Grams} ounce	Pb (%)	Zn (%)
2453	0.0	1.5	1.5	7.20	0.81	0.48
2454	1.5	3.0	1.5	30.17	2.32	1.65
2455	3.0	4.5	1.5	28.46	2.55	3.58
2456	4.5	6.0	1.5	34.29	2.08	3.78
2457	6.0	7.6	1.6	66.51	4.25	6.62
2458	7.6	9.1	1.5	130.97	9.15	16.71
2459	9.1	10.6	1.5	146.06	6.99	12.62
2460	10.6	12.1	1.5	74.74	5.20	10.33
2461	12.1	13.7	1.6	36.34	2.20	4.58
2462	13.7	15.2	1.5	40.46	2.58	5.16
2463	15.2	16.7	1.5	65.49	4.08	10.07
2464	16.7	18.2	1.5	81.77	5.30	12.06
2465	18.2	19.8	1.6	90.86	5.73	12.93
2466	19.8	21.3	1.5	86.74	5.68	10.22
2467	21.3	22.8	1.5	110.06	6.74	13.40
2468	22.8	24.3	1.5	98.81	6.04	8.82
2469	24.3	25.9	1.6	140.23	6.84	12.93
	25.9	38.1	12.2	0.00	0.00	0.00

End of hole

LATITUDE 3N 10843.024
 DEPARTURE 78W 7494.453
 ELEVATION 1130.213

DIP AT COLLAR +60°
 BEARING 226° 53' 41"
 DEPTH 38.1 m (125 ft)

6.0 - 25.9 = 19.9 m (65.3 ft)
 Ag 90.25 g/t
 Pb 5.43%
 Zn 11.59%

E.C.I.

28.4.76 - 28.4.76

ASSAY NUMBER	SECTION		CORE LENGTH (M)	ASSAYS		
	FROM (M)	TO (M)		Ag ^{frames} / _{zone}	Pb %	Zn %
2470	0.0	1.5	1.5	16.11	0.95	0.48
2471	1.5	3.0	1.5	16.11	1.00	1.48
2472	3.0	4.5	1.5	37.37	3.05	2.85
2473	4.5	6.1	1.6	28.46	1.48	2.85
2474	6.1	7.6	1.5	65.49	4.90	6.80
2475	7.6	9.1	1.5	103.89	7.79	10.69
2476	9.1	10.6	1.5	149.14	10.75	16.19
2477	10.6	12.1	1.5	114.17	9.00	18.27
2478	12.1	13.7	1.6	152.26	12.10	21.36
2479	13.7	15.2	1.5	123.09	9.38	16.56
2480	15.2	16.7	1.5	163.20	9.12	17.94
2481	16.7	18.2	1.5	2.06	0.13	1.65
2482	18.2	19.8	1.6	15.09	0.88	2.08
2483	19.8	21.3	1.5	68.57	4.20	8.04
2484	21.3	22.8	1.5	91.89	6.05	8.18
2485	22.8	24.3	1.5	126.17	7.14	14.11
2486	24.3	25.9	1.6	81.60	3.40	8.40
	25.9	39.6	13.7	0.00	0.00	0.00

End of hole

1407

LATITUDE 3N 10844.052
 DEPARTURE 18W 7495.379
 ELEVATION 1130.004

DIP AT CORNER +85° 45'
 BEARING 14° 08' 00"
 DEPTH 39.6m (130 ft)

6.1 - 16.7m = 10.6m (35 ft)

Ag 124.88 g/t.
 Pb 9.03 %
 Zn 15.46 %

6.1m = 25.9 = 19.8m (65 ft)

Ag 96.12 g/t.
 Pb 6.49 %
 Zn 11.50 %

19.8 - 25.9m = 6.1m (20 ft)

Ag 90.55 g/t.
 Pb 5.11 %
 Zn 9.52 %

E.O.J.

28.4.76 - 29.4.76

ASSAY NUMBER	SECTION		CORE LENGTH	ASSAYS		
	FROM (M)	TO (M)		Ag ^{from} from	Pb	Zn
2487	0.0	1.5	1.5	7.20	0.33	0.19
2488	1.5	3.0	1.5	32.23	2.50	1.50
2489	3.0	4.5	1.5	44.23	3.75	4.85
2490	4.5	6.0	1.5	20.23	1.28	2.80
2491	6.0	7.6	1.6	40.46	2.45	4.45
2492	7.6	9.1	1.5	31.20	1.98	3.80
2493	9.1	10.6	1.5	82.63	6.47	11.66
2494	10.6	12.1	1.5	223.89	15.03	23.74
2495	12.1	13.7	1.6	72.69	4.95	11.00
2496	13.7	15.2	1.5	27.43	1.73	3.80
2497	15.2	16.7	1.5	36.34	2.63	5.96
2498	16.7	18.2	1.5	59.31	4.18	9.32
2499	18.2	19.8	1.6	74.74	4.37	8.76
2500	19.8	21.3	1.5	66.51	4.42	12.28
2501	21.3	22.8	1.5	94.63	6.14	13.10
2502	22.8	24.3	1.5	114.17	7.94	11.97
2503	24.3	25.9	1.6	45.26	3.58	6.93
	25.9	45.7	19.8	0.00	0.00	0.00

End of hole

LATITUDE 3N 10844.371
 DEPARTURE 18W 7495.545
 ELEVATION 1129.904

DIP AT COLLAR +65°
 BEARING 41° 39' 23"
 DEPTH 45.7 m (150 ft)

3.0 - 25.9 m = 22.9 m (75 ft)

Ag 68.74 g/t

Pb 4.71%

Zn 8.91%

29.4.76. 2.5.76

ASSAY NUMBER	SECTION		CORE LENGTH (M)	ASSAYS		
	FROM (M)	TO (M)		Ag ^{frames} : _{ton}	Pb%	Zn%
2504	0.0	1.5	1.5	22.29	2.08	1.32
2505	1.5	3.0	1.5	25.37	2.50	1.00
2506	3.0	4.5	1.5	38.40	3.00	1.44
2507	4.5	6.1	1.6	29.14	2.10	0.66
2508	6.1	7.6	1.5	16.11	1.25	0.52
2509	7.6	9.1	1.5	17.14	1.15	0.78
2510	9.1	10.6	1.5	10.97	0.60	0.39
2511	10.6	12.1	1.5	9.94	0.58	0.70
2512	12.1	13.7	1.6	4.11	0.31	0.45
2513	13.7	15.2	1.5	6.17	0.35	0.67
2514	15.2	16.7	1.5	5.14	0.44	0.63
2515	16.7	18.2	1.5	6.17	0.27	0.54
2516	18.2	19.8	1.6	5.14	0.27	0.45
2517	19.8	21.3	1.5	23.31	1.50	2.80
2518	21.3	22.8	1.5	27.43	1.58	1.20
2519	22.8	24.3	1.5	45.26	2.35	3.65
2520	24.3	25.9	1.6	26.40	0.79	1.15
2521	25.9	27.4	1.5	33.26	2.50	3.94
2522	27.4	28.9	1.5	23.31	1.27	1.92
2523	28.9	30.4	1.5	74.74	5.81	7.71
	30.4	40.8	10.4	NOT ASSAYED		
2524	40.8	42.7	1.9	29.14	1.40	2.25
	42.7	63.7	21.0	NOT ASSAYED		
2525	63.7	65.5	1.8	60.34	3.05	5.05
	65.5	103.0	37.5	NOT ASSAYED		
2526	103.0	105.1	2.1	28.46	1.74	2.25
2527	105.1	106.6	1.5	39.43	3.08	3.00
2528	106.6	108.2	1.6	30.17	2.23	2.54
2529	108.2	109.7	1.5	9.94	0.70	0.63
2530	109.7	111.2	1.5	34.29	2.98	3.12
2531	111.2	112.7	1.5	36.34	2.95	3.20
2532	112.7	115.2	2.5	4.11	0.25	0.46
2533	115.2	117.3	2.1	9.94	0.64	1.35
2534	117.3	118.8	1.5	15.09	0.99	1.21
2535	118.8	120.3	1.5	17.14	1.23	2.40
2536	120.3	121.9	1.6	23.31	1.33	1.43

LATITUDE	3N	10842.738	DIP AT COLLAR	- 56° 15'
DEPARTURE	78W	7494.992	BEARING.	224° 08' 42"
ELEVATION		1124.623	DEPTH.	137.3 m (450 ft)

(5.0 ft)
 $28.9 - 30.4 \text{ m} = 1.5 \text{ m}$ Ag 74.74 g/t.
 Pb. 5.81% Zn 7.71%

$63.7 - 65.5 \text{ m} = 1.8 \text{ m} (6.0 \text{ ft})$ Ag 60.34 g/t.
 Pb. 3.05% Zn 5.05%

E.C.I.

ASSAY NUMBER	SECTION		CORE LENGTH (m)	ASSAYS		
	FROM (m)	TO (m)		Ag ^{gross} _{found}	Pb%	Zn%
2537	121.9	123.4	1.5	28.46	1.40	1.55
2538	123.4	124.9	1.5	45.26	2.88	3.90
2539	124.9	126.4	1.5	181.37	10.09	19.85
2540	126.4	128.0	1.6	156.34	9.82	20.36
2541	128.0	129.5	1.5	141.26	8.71	18.60
2542	129.5	131.0	1.5	102.86	7.57	15.47
2543	131.0	132.5	1.5	37.37	1.78	3.38
2544	132.5	134.1	1.6	59.31	2.60	6.03
2545	134.1	135.6	1.5	146.06	9.20	14.85
2546	135.6	137.3	1.7	153.26	9.47	14.00

End of hole

123.4 - 137.3 = 13.9 m (45.6 ft)

Ag 114.16 g/t

Pb 6.87%

Zn 12.95%

2.5.76. 2.5.76

ASSAY NUMBER	SECTION		CORE LENGTH (M)	ASSAYS		
	FROM (M)	TO (M)		Ag ^{found}	Pb %	Zn %
2547	0.0	2.9	2.9	24.34	2.15	1.64
2548	2.9	4.4	1.5	10.97	0.66	0.45
2549	4.4	5.3	0.9	35.31	3.28	2.70
2550	5.3	7.6	2.3	52.46	4.45	7.84
2551	7.6	9.0	1.4	49.37	4.20	7.84
2552	9.0	10.7	1.7	40.46	3.70	5.75
2553	10.7	12.0	1.3	34.29	3.30	3.90
2554	12.0	14.4	2.4	12.00	0.60	0.88
2555	14.4	15.2	0.8	40.46	2.28	4.36
2556	15.2	17.1	1.9	50.40	2.75	4.75
2557	17.1	19.1	2.0	46.29	2.98	6.80
2558	19.1	20.7	1.6	59.31	4.03	9.32
2559	20.7	23.2	2.5	53.49	3.58	7.94
2560	23.2	24.4	1.2	108.00	7.09	10.64
2561	24.4	25.9	1.5	105.94	7.64	10.23
2562	25.9	26.8	0.9	111.09	7.80	12.93
2563	26.8	29.2	2.4	101.83	6.20	12.16
2564	29.2	29.8	0.6	122.06	7.74	12.77
2565	29.8	30.2	0.4	16.11	1.43	1.60
2566	30.2	31.9	1.7	146.06	11.82	23.00
2567	31.9	32.5	0.6	160.46	9.32	15.68
2568	32.5	33.3	0.8	8.91	0.26	0.15
2569	33.3	34.5	1.2	48.34	3.09	5.40
2570	34.5	35.5	1.0	175.54	9.12	13.74
2571	35.5	36.0	0.5	1.03	0.16	0.25
	36.0	38.5	2.5	NOT ASSAYED		
2572	38.5	39.2	0.7	55.54	7.59	17.61
2573	39.2	41.9	2.7	12.00	0.78	1.62
	41.9	121.9	80.0	0.00	0.00	0.00

End of hole

LATITUDE 3N 10841.072
 DEPARTURE 78W 7494.756
 ELEVATION 1126.003
 DIP AT COLLAR +1° 16"
 BEARING 196° 17' 12"
 DEPTH 121.9 m (400 ft)

4.4 - 12.0 m = 7.6 m (25 ft)

Ag 44.07 g/t
 Pb 3.90 %
 Zn 6.09 %

4.4 - 35.5 = 31.1 m (102 ft)

Ag 67.86 g/t
 Pb 4.67 %
 Zn 8.20 %

14.4 - 35.5 = 21.1 m (69 ft)

Ag 82.78 g/t
 Pb 5.41 %
 Zn 9.81 %

4.4 - 39.2 m = 34.8 m (114 ft)

Ag 61.78 g/t
 Pb 4.33 %
 Zn 7.70 %

(E.C.)

4.5.76 - 6.5.76

ASSAY NUMBER	SECTION		CORE LENGTH (M)	ASSAYS		
	FROM (M)	TO (M)		Ag ^{grams} grams	Pb	Zn
	0.0	56.5	56.5	0.00	0.00	0.00
2601	56.5	57.9	1.4	44.23	3.38	3.52
2602	57.9	59.2	1.3	13.03	0.85	1.40
2603	59.2	60.5	1.3	35.31	3.33	5.40
2604	60.5	61.6	1.1	23.31	1.72	1.85
	61.6	67.9	6.3	NOT ASSAYED		
2605	67.9	69.3	1.4	10.97	0.11	0.68
2606	69.3	70.6	1.3	8.91	0.12	0.45
2607	70.6	71.9	1.3	17.14	0.32	1.20
2608	71.9	73.1	1.2	6.17	0.07	1.15
2609	73.1	74.5	1.4	8.23	0.05	0.73
2610	74.5	75.7	1.2	30.17	0.80	1.90
2611	75.7	77.0	1.3	23.31	0.49	1.73
2612	77.0	78.6	1.6	21.26	0.45	1.58
2613	78.6	79.9	1.3	16.11	0.48	1.40
2614	79.9	81.5	1.6	10.97	0.09	0.60
2615	81.5	82.8	1.3	15.09	0.49	2.33
2616	82.8	84.3	1.5	7.20	0.08	0.45
2617	84.3	85.6	1.3	7.20	0.07	0.68
2618	85.6	86.8	1.2	8.91	0.10	0.67
2619	86.8	88.2	1.4	8.91	0.08	0.58
2620	88.2	91.4	3.2	17.14	0.50	0.75
	91.4	96.8	5.4	NOT ASSAYED		
2621	96.8	97.5	0.7	28.46	0.62	1.00
	97.5	103.1	5.6	NOT ASSAYED		
2622	103.1	104.5	1.4	26.40	1.67	2.28
2623	104.5	105.9	1.4	34.29	2.25	2.78
	105.9	107.9	2.0	0.00	0.00	0.00

End of hole

LATITUDE 2N 10602.785
 DEPARTURE 66W. 1732.380
 ELEVATION 1174.983
 DIP AT COLLAR. +8° 30'
 BEARING 147° 35' 00"
 DEPTH 107.9 m (354 ft)

56.5 - 60.5 m = 4.0 m (13 ft)

Ag. 31.19 g/t Pb 2.54% Zn. 3.44%

low

ASSAY NUMBER	SECTION	CORE	ASSAYS
From (m)	To (m)	LENGTH (m)	Ag. Ferrus
2574	0.0	4.8	0.00
	4.8	14.8	0.00
2575	6.9	8.5	2.10
	8.5	1.0	1.82
2576	12.1	3.6	1.64
	13.4	1.3	31.20
	22.2	8.8	2.93
2577	24.6	1.7	0.40
	26.3	1.7	0.64
2578	29.0	2.7	1.30
	31.7	2.7	1.09
	32.4	0.7	0.18
2579	41.1	1.6	0.55
	42.7	1.6	1.12
2580	48.7	2.2	2.03
	50.9	2.2	2.26
2581	53.7	2.8	0.13
	56.5	2.8	0.33
2582	55.2	1.5	5.15
	56.7	1.5	105.94
2583	56.7	0.9	2.35
	57.6	0.9	2.914
2584	57.6	2.0	2.70
2585	59.6	0.9	3.80
	60.5	0.9	4.30
2586	61.0	0.5	6.10
	61.5	0.5	9.22
2587	61.5	0.5	3.18
	62.0	0.5	4.70
2588	63.6	1.5	3.18
	65.1	1.5	4.26
2589	65.5	0.6	3.18
	66.1	0.6	4.70
2590	67.1	1.5	8.70
	68.6	1.5	11.66
2591	68.6	1.5	4.83
	70.1	1.5	4.83
2592	68.6	1.5	3.88
	70.1	1.5	8.17
2593	70.1	1.5	4.60
	71.6	1.5	7.82
2594	71.6	1.5	4.65
	73.1	1.5	7.61
2595	73.1	1.5	4.65
	74.6	1.5	8.50
2596	74.6	1.5	5.20
	76.1	1.5	8.50
2597	76.1	1.5	8.50
2598	77.5	1.1	3.38
	78.6	1.1	6.57
2599	78.6	0.9	5.87
	79.5	0.9	11.66
2600	79.5	2.1	2.03
	81.6	2.1	2.75
2701	81.6	0.7	0.13
	82.3	0.7	0.33
2702	82.3	0.6	2.50
	82.9	0.6	4.10
2703	82.9	2.1	0.53
	85.0	2.1	0.89
2704	85.0	1.4	0.98
	86.4	1.4	0.98
2705	86.4	1.6	2.53
	88.0	1.6	2.35

Ag Ferrus

Ag Ferrus

Ag Ferrus

Ag Ferrus

ASSAYS

CORE

SECTION

ASSAY



LATITUDE 10843.472 DIP AT COLLAR -75° 25'
DEPARTURE 7495.470 BEARING 39° 40' 18"
ELEVATION 1124.589 DEPTH 170.7 m (560 ft)

53.7 - 56.7 = 3.0m (10ft) Ag 95.83 g/t
 Pb 5.17% Zn 8.25%

59.6 - 74.5 = 14.9m (49ft)
 Ag 83.63 g/t
 Pb 5.03%
 Zn 8.22%

53.7 - 74.5 = 20.8m (68ft)
 Ag 78.73 g/t
 Pb 4.35%
 Zn 7.08%

127.5 - 131.6 = 4.1m (13.5ft)
 Ag 51.62 g/t Pb 3.24%
 Zn 5.73%

132.3 - 132.9 = 0.6m (2ft) Ag 42.51 g/t Pb 2.50% Zn 4.10% **NOW**

7.5.76 - 8.5.76.

ASSAY NUMBER	SECTION		CORE LENGTH (M)	ASSAYS		
	FROM (M)	TO (M)		Ag ^{frame} stone	Pb %	Zn %
2624	0.0 ✓	18.3 ✓	18.3	80.00	0.00	0.00
	18.3 ✓	21.1 ✓	2.8	8.91	0.30	1.20
	21.1 ✓	27.4 ✓	6.3	NOT ASSAYED.		
2625	27.4 ✓	29.3 ✓	1.9	50.40	3.90	5.00
2626	29.3 ✓	30.5 ✓	1.2	83.66	5.15	7.05
2627	30.5 ✓	32.0 ✓	1.5	73.71	4.60	5.85
2628	32.0 ✓	32.8 ✓	0.8	86.74	6.92	10.21
2629	32.8 ✓	34.3 ✓	1.5	57.60	4.30	5.10
2630	34.3 ✓	36.4 ✓	2.1	183.43	12.04	12.77
2631	36.4 ✓	38.5 ✓	2.1	40.46	2.70	1.60
2632	38.5 ✓	41.1 ✓	2.6	32.23	1.95	1.15
2633	41.1 ✓	42.7 ✓	1.6	20.23	1.20	0.25
	42.7 ✓	65.5 ✓	22.8	0.00	0.00	0.00

End of hole

LATITUDE 2N. 10602.158
 DEPARTURE 66W. 1731.638
 ELEVATION. 1175.064

DIP AT COLLAR. +5°40'
 BEARING 169°08'00"
 DEPTH. 65.5 m (215 ft.)

27.4 - 36.4 = 9.0 m (29.5 ft)

Ag 94.18 g/t.

Pb 6.42%

Zn 6.80%

9.5.76 - 15.5.76

ASSAY NUMBER	SECTION		CORE LENGTH (M)	ASSAYS		
	FROM (M)	TO (M)		Ag ^{found} / Ag ^{total}	Pb (%)	Zn (%)
2707	0.0 ✓	1.6 ✓	1.6 ✓	0.00	0.00	0.00
	1.6 ✓	4.6 ✓	3.0 ✓	9.94 ✓	0.98 ✓	1.00 ✓
	4.6 ✓	12.2 ✓	7.6 ✓	NOT ASSAYED		
2708	12.2 ✓	13.7 ✓	1.5 ✓	30.17 ✓	2.55 ✓	4.00 ✓
	13.7 ✓	65.6 ✓	51.9 ✓	NOT ASSAYED		
2709	65.6 ✓	68.6 ✓	3.0 ✓	21.26 ✓	1.21 ✓	1.60 ✓
2710	68.6 ✓	70.1 ✓	1.5 ✓	25.37 ✓	1.88 ✓	2.50 ✓
2711	70.1 ✓	71.6 ✓	1.5 ✓	24.34 ✓	0.15 ✓	0.60 ✓
2712	71.6 ✓	73.2 ✓	1.6 ✓	101.83 ✓	5.75 ✓	10.05 ✓
2713	73.2 ✓	74.7 ✓	1.5 ✓	105.94 ✓	7.80 ✓	14.42 ✓
2714	74.7 ✓	76.2 ✓	1.5 ✓	30.17 ✓	1.53 ✓	1.60 ✓
2715	76.2 ✓	77.7 ✓	1.5 ✓	8.23 ✓	0.07 ✓	0.27 ✓
2716	77.7 ✓	79.2 ✓	1.5 ✓	9.94 ✓	0.20 ✓	0.75 ✓
2717	79.2 ✓	80.8 ✓	1.6 ✓	24.34 ✓	0.80 ✓	0.55 ✓
2718	80.8 ✓	82.3 ✓	1.5 ✓	5.14 ✓	0.11 ✓	0.41 ✓
2719	82.3 ✓	83.8 ✓	1.5 ✓	97.72 ✓	5.83 ✓	8.62 ✓
2720	83.8 ✓	85.3 ✓	1.5 ✓	44.23 ✓	2.70 ✓	3.75 ✓
2721	85.3 ✓	88.4 ✓	3.1 ✓	13.03 ✓	1.05 ✓	1.45 ✓
	88.4 ✓	90.0 ✓	1.6 ✓	NOT ASSAYED		
2722	90.0 ✓	92.9 ✓	2.9 ✓	12.00 ✓	0.65 ✓	0.88 ✓
2723	92.9 ✓	94.4 ✓	1.5 ✓	19.20 ✓	1.35 ✓	1.67 ✓
2724	94.4 ✓	96.0 ✓	1.6 ✓	21.26 ✓	1.38 ✓	1.44 ✓
2725	96.0 ✓	97.5 ✓	1.5 ✓	8.91 ✓	0.55 ✓	0.60 ✓
2726	97.5 ✓	99.0 ✓	1.5 ✓	27.43 ✓	2.03 ✓	2.40 ✓
2727	99.0 ✓	100.5 ✓	1.5 ✓	12.00 ✓	0.83 ✓	1.25 ✓
2728	100.5 ✓	102.5 ✓	2.0 ✓	31.20 ✓	2.23 ✓	4.20 ✓
2729	102.5 ✓	103.6 ✓	1.1 ✓	81.60 ✓	4.90 ✓	7.70 ✓
2730	103.6 ✓	105.1 ✓	1.5 ✓	63.43 ✓	6.29 ✓	7.52 ✓
2731	105.1 ✓	106.6 ✓	1.5 ✓	93.94 ✓	4.98 ✓	6.73 ✓
2732	106.6 ✓	108.2 ✓	1.6 ✓	90.85 ✓	4.73 ✓	1.90 ✓
	108.2 ✓	123.0 ✓	14.8 ✓	NOT ASSAYED		
2733	123.0 ✓	125.2 ✓	2.2 ✓	78.86 ✓	6.06 ✓	6.63 ✓
	125.2 ✓	132.6 ✓	7.4 ✓	NOT ASSAYED		

DDH U 77.

Continued on Pages 164 & 165

LATITUDE 2N 10844.451

DIP AT COLLAR $\rightarrow 55^{\circ} 37'$

DEPARTURE 18W 7496.313

BEARING ~~229^{\circ} 42' 32"~~ 44-00

ELEVATION 1124.893

DEPTH 167.6 m (550 ft)

$$71.6 - 74.7 = 3.1 \text{ m (10 ft)}$$

Ag. 103.82 g/t. Pb 6.74% Zn 12.08%

$$82.3 - 83.5 = 1.2 \text{ m (4.9 ft)} \quad \text{Ag. 97.72 g/t. Pb 5.83% Zn 8.62%}$$

$$82.3 - 85.3 = 3.0 \text{ m (10.0 ft)}$$

Ag. 70.98 g/t. Pb 4.27% Zn 6.19%

$$100.5 - 108.2 = 7.7 \text{ m (25.25 ft)}$$

$$102.5 - 106.6 = 4.1 \text{ m (13.5 ft)} \quad \text{Ag. 79.47 g/t}$$

Pb 5.44%

Zn 7.28%

Ag 69.3 g/t

Pb 4.46%

Zn 5.36%

$$123.0 - 125.2 = 2.2 \text{ m (7.2 ft)} \quad \text{Ag 78.86 g/t}$$

Pb 6.06% Zn 6.63%

E.C.I.

ASSAY NUMBER	SECTION		CORE LENGTH (M)	ASSAYS		
	FROM (M)	TO (M)		Ag ^{found}	Pb %	Zn %
2734	132.6	134.1	1.5	66.51	4.18	6.89
2735	134.1	135.6	1.5	34.29	2.20	4.25
2736	135.6	137.1	1.5	43.54	2.98	2.90
2737	137.1	138.6	1.5	63.43	5.46	5.71
2738	138.6	140.2	1.6	87.77	6.96	9.94
2739	140.2	141.7	1.5	18.09	1.23	2.78
2740	141.7	143.2	1.5	5.14	0.08	1.22
2741	143.2	145.5	2.3	50.40	3.75	4.55
	145.5	163.0	17.5	0.00	0.00	0.00
2742	163.0	163.7	0.7	22.29	1.50	1.78
	163.7	167.6	3.9	0.00	0.00	0.00

End of hole.

132.6 - 140.2 = 7.6 m (25 ft)

Ag 59.49 g/t

Pb 4.39%

Zn 5.99%

132.6 - 145.5 = 12.9 m (42.32 ft)

Ag 46.38 g/t

Pb 3.41%

Zn 4.81%

8.5.76 - 9.5.76

ASSAY NUMBER	SECTION		CORE LENGTH (m)	ASSAYS		
	FROM (m)	TO (m)		Ag ^{frame} per tonne	Pb	Zn
2634	0.0 ✓	38.1 ✓	38.1	0.00	0.00	0.00
	38.1 ✓	39.6 ✓	1.5	17.14 ✓	0.25 ✓	1.20 ✓
	39.6 ✓	44.2 ✓	4.6	NOT ASSAYED		
2635	44.2 ✓	45.7 ✓	1.5	9.94 ✓	0.05 ✓	1.00 ✓
	45.7 ✓	50.3 ✓	4.6	NOT ASSAYED		
2636	50.3 ✓	51.8 ✓	1.5	5.14 ✓	0.05 ✓	0.62 ✓
	51.8 ✓	56.1 ✓	4.3	NOT ASSAYED		
2637	56.1 ✓	57.6 ✓	1.5	26.40 ✓	0.40 ✓	0.42 ✓
	57.6 ✓	64.0 ✓	6.4	NOT ASSAYED		
2638	64.0 ✓	65.5 ✓	1.5	4.11 ✓	0.05 ✓	0.25 ✓
	65.5 ✓	70.1 ✓	4.6	NOT ASSAYED		
2639	70.1 ✓	71.6 ✓	1.5	9.94 ✓	0.06 ✓	0.37 ✓
	71.6 ✓	77.7 ✓	6.1	NOT ASSAYED		
2640	77.7 ✓	79.2 ✓	1.5	8.23 ✓	0.14 ✓	0.75 ✓
	79.2 ✓	83.8 ✓	4.6	NOT ASSAYED		
2641	83.8 ✓	85.3 ✓	1.5	18.17 ✓	0.11 ✓	0.55 ✓
	85.3 ✓	89.9 ✓	4.6	NOT ASSAYED		
2642	89.9 ✓	91.4 ✓	1.5	9.94 ✓	0.09 ✓	0.25 ✓
	91.4 ✓	94.9 ✓	3.5	NOT ASSAYED		
2643	94.9 ✓	96.5 ✓	1.6	28.46 ✓	1.73 ✓	2.20 ✓
2644	96.5 ✓	97.8 ✓	1.3	20.23 ✓	0.66 ✓	1.28 ✓
2645	97.8 ✓	99.4 ✓	1.6	9.94 ✓	0.13 ✓	0.75 ✓
	99.4 ✓	106.7 ✓	7.3	0.00	0.00	0.00

End of hole

LATITUDE 2N 10603.298
 DEPARTURE 66W 7732.983
 ELEVATION 1175.072
 DIP AT COLLAR 8° 50'
 BEARING 133° 31' 00"
 DEPTH 106.7m (350ft)



15.5.76 - 16.5.76

ASSAY NUMBER	SECTION		CORE LENGTH (M)	ASSAYS		
	FROM (M)	TO (M)		Ag ^{Frame} Frame	PbZn	Zn
2743	0.0 ✓	1.5 ✓	1.5	18.17 ✓	1.37 ✓	1.00 ✓
2744	1.5 ✓	3.0 ✓	1.5	8.91 ✓	0.44 ✓	0.24 ✓
2745	3.0 ✓	4.6 ✓	1.6	9.94 ✓	0.50 ✓	0.14 ✓
2746	4.6 ✓	6.1 ✓	1.5	35.31 ✓	3.40 ✓	1.78 ✓
2747	6.1 ✓	7.6 ✓	1.5	30.17 ✓	2.93 ✓	2.63 ✓
2748	7.6 ✓	9.1 ✓	1.5	32.22 ✓	3.15 ✓	1.30 ✓
2749	9.1 ✓	10.7 ✓	1.6	29.14 ✓	3.10 ✓	1.00 ✓
2750	10.7 ✓	12.2 ✓	1.5	19.20 ✓	1.53 ✓	0.30 ✓
2751	12.2 ✓	13.7 ✓	1.5	28.45 ✓	1.25 ✓	0.26 ✓
2752	13.7 ✓	15.2 ✓	1.5	16.11 ✓	0.73 ✓	0.38 ✓
2753	15.2 ✓	16.8 ✓	1.6	31.20 ✓	2.88 ✓	3.45 ✓
2754	16.8 ✓	18.3 ✓	1.5	29.14 ✓	2.60 ✓	1.32 ✓
2755	18.3 ✓	19.8 ✓	1.5	23.31 ✓	1.89 ✓	1.56 ✓
2756	19.8 ✓	21.3 ✓	1.5	26.40 ✓	2.38 ✓	2.86 ✓
2757	21.3 ✓	22.9 ✓	1.6	24.34 ✓	1.85 ✓	0.63 ✓
2758	22.9 ✓	24.4 ✓	1.5	48.34 ✓	4.35 ✓	4.40 ✓
2759	24.4 ✓	25.9 ✓	1.5	40.45 ✓	3.30 ✓	3.80 ✓
2760	25.9 ✓	27.4 ✓	1.5	58.62 ✓	3.65 ✓	4.40 ✓
2761	27.4 ✓	29.0 ✓	1.5	89.82 ✓	5.20 ✓	4.95 ✓
2762	29.0 ✓	30.5 ✓	1.6	45.25 ✓	2.30 ✓	2.54 ✓
2763	30.5 ✓	32.0 ✓	1.5	48.34 ✓	2.70 ✓	3.06 ✓
2764	32.0 ✓	33.5 ✓	1.5	62.40 ✓	4.68 ✓	7.45 ✓
2765	33.5 ✓	35.1 ✓	1.6	40.45 ✓	2.43 ✓	2.10 ✓
2766	35.1 ✓	36.6 ✓	1.5	95.65 ✓	5.00 ✓	9.28 ✓
36.6	36.6	64.0	27.4	NOT ASSAYED		
2767	64.0 ✓	65.5 ✓	1.5	70.62 ✓	6.16 ✓	8.64 ✓
2768	65.5 ✓	67.1 ✓	1.6	54.51 ✓	3.90 ✓	7.14 ✓
2769	67.1 ✓	68.6 ✓	1.5	113.14 ✓	8.24 ✓	13.78 ✓
2770	68.6 ✓	70.1 ✓	1.5	132.00 ✓	9.10 ✓	13.22 ✓
2771	70.1 ✓	71.6 ✓	1.5	127.20 ✓	7.92 ✓	8.52 ✓
2772	71.6 ✓	73.2 ✓	1.6	115.88 ✓	6.18 ✓	9.34 ✓
2773	73.2 ✓	74.7 ✓	1.5	118.97 ✓	5.31 ✓	7.67 ✓
2774	74.7 ✓	76.2 ✓	1.5	114.85 ✓	5.35 ✓	7.18 ✓
2775	76.2 ✓	77.7 ✓	1.5	95.65 ✓	4.28 ✓	6.72 ✓
2776	77.7 ✓	79.2 ✓	1.5	110.05 ✓	6.57 ✓	10.25 ✓
	79.2 ✓	97.5 ✓	18.3	0.00	0.00	0.00

End of hole.

LATITUDE	3N	10841.867	DIP AT COLLAR	-29°51'
DEPARTURE	78W	7494.408	BEARING	218°23'55"
ELEVATION		1125.110	DEPTH	97.5 m. (320 ft.)

$$22.9 - 36.6 = 13.7 \text{ m (45 ft)}$$

Ag 58.59 g/t.

Pb 3.71%

Zn 4.62%

$$64.0 - 79.2 = 15.2 \text{ m (50 ft)}$$

Ag 105.03 g/t

Pb 6.28%

Zn 9.23%

10.5.76 · 11.5.76

ASSAY NUMBER	SECTION		CORE LENGTH (M)	ASSAYS			DEPT	ELEV
	FROM (M)	TO (M)		Ag ^{frames} / tonne	Pb %	Zn %		
2646	0.0 ✓	1.5 ✓	1.5	34.29 ✓	0.82 ✓	0.35 ✓		
2647	1.5 ✓	3.0 ✓	1.5	52.46 ✓	2.45 ✓	1.05 ✓		
2648	3.0 ✓	4.6 ✓	1.6	50.40 ✓	1.98 ✓	1.10 ✓		
2649	4.6 ✓	5.5 ✓	0.9	21.26 ✓	0.80 ✓	0.59 ✓		
	5.5 ✓	6.4 ✓	0.9	NOT ASSAYED				
2650	6.4 ✓	7.6 ✓	1.2	8.91 ✓	0.23 ✓	4.00 ✓		
2651	7.6 ✓	9.1 ✓	1.5	15.09 ✓	0.40 ✓	2.83 ✓		
2652	9.1 ✓	10.7 ✓	1.6	21.26 ✓	0.83 ✓	4.70 ✓		
2653	10.7 ✓	12.2 ✓	1.5	39.43 ✓	2.05 ✓	5.00 ✓		
2654	12.2 ✓	13.7 ✓	1.5	28.46 ✓	1.52 ✓	3.88 ✓		10
2655	13.7 ✓	15.2 ✓	1.5	28.46 ✓	1.77 ✓	5.65 ✓		
2656	15.2 ✓	16.8 ✓	1.6	72.69 ✓	5.20 ✓	7.11 ✓		
2657	16.8 ✓	18.3 ✓	1.5	37.37 ✓	2.40 ✓	5.15 ✓		
2658	18.3 ✓	19.8 ✓	1.5	34.29 ✓	2.10 ✓	4.38 ✓		
2659	19.8 ✓	21.3 ✓	1.5	30.17 ✓	2.10 ✓	2.88 ✓		
2660	21.3 ✓	22.9 ✓	1.6	16.11 ✓	1.00 ✓	2.55 ✓		
2661	22.9 ✓	24.4 ✓	1.5	21.26 ✓	1.29 ✓	2.43 ✓		
2662	24.4 ✓	25.9 ✓	1.5	19.20 ✓	1.04 ✓	2.92 ✓		
2663	25.9 ✓	27.4 ✓	1.5	17.14 ✓	1.05 ✓	2.65 ✓		
2664	27.4 ✓	29.0 ✓	1.6	50.40 ✓	3.35 ✓	6.07 ✓		27.4
2665	29.0 ✓	30.5 ✓	1.5	56.57 ✓	3.30 ✓	8.49 ✓		Ag
2666	30.5 ✓	32.0 ✓	1.5	39.43 ✓	2.50 ✓	5.48 ✓		
2667	32.0 ✓	33.5 ✓	1.5	22.29 ✓	1.45 ✓	1.65 ✓		
2668	33.5 ✓	35.1 ✓	1.6	9.94 ✓	0.15 ✓	1.18 ✓		
2669	35.1 ✓	36.6 ✓	1.5	13.03 ✓	0.35 ✓	1.40 ✓		
2670	36.6 ✓	38.1 ✓	1.5	22.29 ✓	1.14 ✓	1.95 ✓		
2671	38.1 ✓	39.6 ✓	1.5	37.37 ✓	2.65 ✓	4.50 ✓		
2672	39.6 ✓	41.1 ✓	1.5	65.49 ✓	5.65 ✓	9.52 ✓		
2673	41.1 ✓	42.7 ✓	1.6	52.46 ✓	3.45 ✓	5.15 ✓		38
2674	42.7 ✓	44.2 ✓	1.5	89.83 ✓	4.95 ✓	2.95 ✓		
2675	44.2 ✓	45.7 ✓	1.5	65.49 ✓	4.40 ✓	8.98 ✓		
2676	45.7 ✓	47.2 ✓	1.5	35.31 ✓	2.43 ✓	2.13 ✓		
2677	47.2 ✓	48.8 ✓	1.6	71.66 ✓	5.65 ✓	4.30 ✓		
2678	48.8 ✓	50.3 ✓	1.5	32.23 ✓	2.33 ✓	3.80 ✓		
2679	50.3 ✓	51.8 ✓	1.5	26.40 ✓	1.45 ✓	3.78 ✓		
2680	51.8 ✓	53.3 ✓	1.5	79.69 ✓	5.25 ✓	5.20 ✓		
2681	53.3 ✓	54.9 ✓	1.6	39.43 ✓	2.78 ✓	4.90 ✓		
2682	54.9 ✓	56.4 ✓	1.5	50.40 ✓	3.05 ✓	6.70 ✓		
2683	56.4 ✓	57.9 ✓	1.5	39.43 ✓	3.00 ✓	6.98 ✓		
2684	57.9 ✓	59.4 ✓	1.5	20.23 ✓	1.00 ✓	2.53 ✓		
2685	59.4 ✓	60.5 ✓	1.1	55.54 ✓	3.43 ✓	7.80 ✓		
End of hole	60.5 ✓	76.2 ✓	15.7	0.00	0.00	0.00		

LATITUDE SN 10776.534
 DEPARTURE 12W 7687.983
 ELEVATION 1154.798

DIP AT COLLAR +10° 05'
 BEARING 154° 50' 32"
 DEPTH 76.2 m (250 ft)

$$10.7 - 19.8 \text{ m} = 9.1 \text{ m (30.0 ft)}$$

Ag 40.47 g/t

Pb 2.54%

Zn 5.22%

$$27.4 - 32.0 = 4.6 \text{ m (15.0 ft)}$$

Ag 48.83 g/t Pb 3.06%

Zn 6.67%

$$38.1 - 60.5 = 22.4 \text{ m (73.5 ft)}$$

Ag 50.00 g/t

Pb 3.40%

Zn 5.23%

E.C.J.

18.5.76 - 18.5.76

ASSAY NUMBER	SECTION		CORE LENGTH (M)	ASSAYS		
	FROM (M)	TO (M)		Ag ^{found} tan	Pb (%)	Zn (%)
	0.0	9.1	9.1	0.00	0.00	0.00
2777	9.1	10.7	1.6	59.31	3.38	5.60
2778	10.7	12.2	1.5	68.57	4.35	5.40
2779	12.2	15.2	3.0	45.25	2.95	2.38
2780	15.2	18.3	3.1	16.11	1.61	1.15
2781	18.3	21.3	3.0	19.20	1.62	0.85
2782	21.3	24.4	3.1	22.28	2.03	0.78
2783	24.4	27.4	3.0	18.17	1.55	1.95
	27.4	38.1	10.7	0.00	0.00	0.00

End of hole.

LATITUDE SN 10835.044.
 DEPARTURE 12W 76W? 7570.330
 ELEVATION 1137.789.

DIP AT COLLAR -90°
 BEARING
 DEPTH 38.1m (125ft).

9.1 - 12.2m = 3.1m (10ft) Ag. 63.79 g/t.
 Pb. 3.85% Zn 5.5%

12.5.76 - 12.5.76

ANTITUDE SN 1076.094
DEPARTURE TAM. 7086.964
ELEVATION 1154.668
DIP AT CORNER + 09° 38'
BEARING 186° 54' 00"
DEPTH 45.7m (150 ft)

27-4-9 = 2.2m (7.23ft) Ag. 30.34 g/c
 Pb 2.587 Zn 5.397

11.4 - 16.8 = 5.4m (17.72 ft)
 Ag 32.89 g/c
 Pb 2.15
 Zn 4.14

LOW

15.2 - 16.8 = 1.6m (5.25ft) Ag. 31.20 g/c Pb 8.05 Zn 4.95

24.4 - 33.5 = 9.1m (30 ft)
 Ag 69.11 g/c
 Pb 4.36
 Zn 5.13

Ag 69.12 g/c
 Pb 4.03
 Zn 4.94

ASSAY NUMBER	SECTION	Core	LENGTH (M)	FROM (M)	ASSAYS
2686		2.7	4.9	2.2	36.34 Ag 2.58 Pb 2.7 Zn 5.39
2687		6.9	9.1	2.2	13.03 Ag 0.84 Pb 1.83 Zn 1.83
2688		9.1	11.4	2.3	19.20 Ag 1.03 Pb 3.48 Zn 3.48
2689		11.4	13.7	2.3	29.14 Ag 2.05 Pb 3.70 Zn 3.70
2690		13.7	15.2	1.5	40.46 Ag 2.40 Pb 3.95 Zn 3.95
2691		15.2	16.8	1.6	31.20 Ag 2.05 Pb 4.95 Zn 4.95
2692		16.8	18.3	1.5	18.17 Ag 1.15 Pb 2.28 Zn 2.28
2693		18.3	19.8	1.5	20.23 Ag 1.15 Pb 3.00 Zn 3.00
2694		19.8	21.3	1.5	15.09 Ag 0.91 Pb 3.20 Zn 3.20
2695		21.3	22.9	1.6	27.43 Ag 1.48 Pb 2.80 Zn 2.80
2696		22.9	24.4	1.5	41.49 Ag 2.05 Pb 3.80 Zn 3.80
2697		24.4	25.9	1.5	112.12 Ag 6.29 Pb 11.52 Zn 11.52
2698		25.9	27.4	1.5	60.34 Ag 2.88 Pb 5.82 Zn 5.82
2699		27.4	29.0	1.6	61.37 Ag 3.40 Pb 5.50 Zn 5.50
2700		29.0	30.5	1.5	61.37 Ag 4.28 Pb 3.15 Zn 3.15
2801		30.5	32.0	1.5	50.48 Ag 3.92 Pb 1.74 Zn 1.74
2802		32.0	33.5	1.5	69.60 Ag 5.48 Pb 3.02 Zn 3.02
2803		33.5	35.1	1.6	2.05 Ag 0.14 Pb 0.86 Zn 0.86
2804		35.1	36.6	1.5	7.88 Ag 0.53 Pb 0.20 Zn 0.20
2805		36.6	38.1	1.5	3.08 Ag 0.20 Pb 0.10 Zn 0.10
2806		38.1	39.6	1.5	9.94 Ag 0.63 Pb 0.82 Zn 0.82
2807		39.6	41.1	1.5	5.14 Ag 0.28 Pb 0.82 Zn 0.82
2808		41.1	42.5	1.4	5.14 Ag 0.45 Pb 1.42 Zn 1.42
2809		42.5	44.2	1.7	0.34 Ag 0.15 Pb 0.34 Zn 0.34
2810		44.2	45.7	1.5	23.31 Ag 1.28 Pb 2.64 Zn 2.64

End of hole

(E.C.J.)

18.5.76 . 20.5.76

ASSAY NUMBER	SECTION		CORE LENGTH (M)	ASSAYS		
	FROM (M)	TO (M)		Ag ^{grams}	Pb %	Zn %
	0.0	6.0	6.0	0.00	0.00	0.00
2784	6.0	7.6	1.6	63.42	3.83	6.40
2785	7.6	9.1	1.5	14.05	0.75	1.75
2786	9.1	10.7	1.6	18.17	1.05	1.20
2787	10.7	12.2	1.5	17.14	1.35	2.10
2788	12.2	13.7	1.5	18.17	1.08	1.40
2789	13.7	15.2	1.5	15.08	1.00	1.78
2790	15.2	16.8	1.6	56.57	3.60	7.28
2791	16.8	18.3	1.5	46.68	6.92	12.91
2792	18.3	19.8	1.5	55.54	3.48	7.44
2793	19.8	21.3	1.5	128.22	7.81	15.59
2794	21.3	22.9	1.6	103.88	6.62	12.81
2795	22.9	24.4	1.5	66.51	4.59	8.56
	24.4	38.1	13.7	0.00	0.00	0.00

End of hole

LATITUDE 10835.153

DIP AT COLLAR +90°

DEPARTURE 7510.732

BEARING

ELEVATION 1142.061

DEPTH 38.1m (125 ft)

6.0 - 7.6 = 1.6m (5.25 ft) Ag 63.42 g/t. Pb 3.83% Zn 6.40%

15.2 - 24.4m = 9.2m (30 ft)

Ag 84.74 g/t.

Pb 5.49%

Zn 10.76%

(E.C.J.)

13.5.76 - 14.5.76

ASSAY NUMBER	SECTION		CORE LENGTH	ASSAYS		
	FROM (M)	TO (M)		Ag ^{grams} / _{ounce}	Pb %	Zn %
2811	0.0 ✓	3.0 ✓	3.0	66.51 ✓	5.51 ✓	6.68 ✓
2812	3.0 ✓	4.6 ✓	1.6	56.57 ✓	3.80 ✓	8.13 ✓
2813	4.6 ✓	6.2 ✓	1.6	61.37 ✓	3.83 ✓	7.96 ✓
2814	6.2 ✓	10.2 ✓	4.0	0.34 ✓	0.05 ✓	0.14 ✓
2815	10.2 ✓	12.5 ✓	2.3	136.12 ✓	8.27 ✓	13.41 ✓
2816	12.5 ✓	13.0 ✓	0.5	2.06 ✓	0.10 ✓	2.10 ✓
2817	13.0 ✓	13.7 ✓	0.7	99.77 ✓	6.99 ✓	14.17 ✓
2818	13.7 ✓	15.2 ✓	1.5	156.34 ✓	8.37 ✓	13.51 ✓
2819	15.2 ✓	16.9 ✓	1.7	149.14 ✓	8.59 ✓	16.37 ✓
2820	16.9 ✓	17.3 ✓	0.4	2.06 ✓	0.05 ✓	0.22 ✓
2821	17.3 ✓	18.6 ✓	1.3	77.83 ✓	4.25 ✓	9.69 ✓
	18.6 ✓	41.1 ✓	22.5	NOT ASSAYED		
2822	41.1 ✓	42.7 ✓	1.6	111.09 ✓	8.32 ✓	10.89 ✓
2823	42.7 ✓	44.2 ✓	1.5	106.97 ✓	7.16 ✓	12.41 ✓
2824	44.2 ✓	45.7 ✓	1.5	84.68 ✓	5.20 ✓	13.11 ✓
2825	45.7 ✓	47.2 ✓	1.5	73.71 ✓	4.79 ✓	9.87 ✓
2826	47.2 ✓	48.8 ✓	1.6	66.51 ✓	4.08 ✓	8.46 ✓
2827	48.8 ✓	50.3 ✓	1.5	78.85 ✓	4.50 ✓	8.56 ✓
2828	50.3 ✓	51.8 ✓	1.5	75.77 ✓	5.20 ✓	7.69 ✓
2829	51.8 ✓	53.3 ✓	1.5	100.80 ✓	7.34 ✓	9.41 ✓
2830	53.3 ✓	54.9 ✓	1.6	74.74 ✓	4.30 ✓	7.64 ✓
	54.9 ✓	76.2 ✓	21.3	0.00	0.00	0.00

End of hole

LATITUDE SN 10780.559
 DEPARTURE TRW 7687.547
 ELEVATION 1153.227

DIP AT COLLAR -55° 03'
 BEARING 49° 27' 00"
 DEPTH 76.2 m (250 ft)

0 - 18.6 = 18.6 m (61 ft)

Ag 73.31 g/t
 Pb 4.60 %
 Zn 8.00 %

41.1 - 54.9 = 13.8 m (45 ft)

Ag 85.86 g/t
 Pb 5.65 %
 Zn 9.77 %

(E.C.J.)

20.5.76 - 21.5.76

ASSAY NUMBER	SECTION		CORE LENGTH (M)	ASSAYS		
	FROM (M)	TO (M)		Ag ^{grams} / _{tonne}	Pb%	Zn%
	0.0	7.6	7.6	0.00	0.00	0.00
2796	7.6	9.1	1.5	17.14	0.83	1.00
2797	9.1	10.7	1.6	13.03	0.63	1.13
2798	10.7	12.2	1.5	16.11	0.93	1.93
2799	12.2	13.7	1.5	10.97	0.58	1.20
2900	13.7	15.2	1.5	62.40	4.10	8.96
2901	15.2	16.8	1.6	114.17	7.12	17.45
2902	16.8	18.3	1.5	120.00	7.22	22.48
2903	18.3	19.8	1.5	87.77	5.32	17.28
2904	19.8	21.3	1.5	98.74	6.40	11.30
2905	21.3	23.2	1.9	84.69	5.63	11.09
	23.2	44.2	19.0 ^{21.0}	0.00	0.00	0.00

End of hole

LATITUDE 10834.141
 DEPARTURE 7570.116
 ELEVATION 1142.226
 DIP AT COLLAR +65° 7'
 BEARING 227° 02' 14"
 DEPTH 44.2 m (145 ft)

13.7 - 23.2 = 9.5 m (31.0 ft)
 Ag 94.42 g/t.
 Pb 5.96%
 Zn 15.53%

E.C.J.

15.5.76 - 16.5.76

ASSAY NUMBER	SECTION		CORE LENGTH	ASSAYS		
	FROM (M)	TO (M)		Ag ^{grams} tonne	Pb%	Zn%
2832	6.1	7.6	1.5	116.91	6.70	17.88
			0.3	NOT ASSAYED		
2833	7.9	9.1	1.2	100.80	5.00	17.62
2834		9.8	0.7	70.62	4.28	9.58
			44.6	NOT ASSAYED		
2835	54.4	55.4	1.0	69.60	4.25	6.84
			35.6	NOT ASSAYED		
2836	81.0	82.3	1.3	40.45	2.68	5.00
2837		83.8	1.5	39.42	2.45	4.10
2838		85.3	1.5	9.94	0.78	0.52

SEE BELOW

2831	0.0	3.3	3.3	59.31	3.65	8.15
	3.3	6.1	2.8	NOT ASSAYED		
2832	6.1	7.6	1.5	116.91	6.70	17.88
	7.6	7.9	0.3	NOT ASSAYED		
2833	7.9	9.1	1.2	100.80	5.00	17.62
2834	9.1	9.8	0.7	70.62	4.28	9.58
	9.8	54.4	44.6	NOT ASSAYED		
2835	54.4	55.4	1.0	69.60	4.25	6.84
	55.4	81.0	25.6	NOT ASSAYED		
2836	81.0	82.3	1.3	40.45	2.68	5.00
2837	82.3	83.8	1.5	39.42	2.45	4.10
2838	83.8	85.3	1.5	9.94	0.78	0.52
	85.3	94.5	9.2	0.00	0.00	0.00

End of hole

LATITUDE 5N 10782.364
 DEPARTURE 72W. 7693.25
 ELEVATION 1153.994

DIP AT COLLAR -31° 12'
 BEARING 41° 12' 47"
 DEPTH 94.5 m. (310 ft)

6.1 - 9.8 m = 3.7 m (12.4 ft)
 Ag 93.43 g/t
 Pb 5.15%
 Zn 14.78%

54.4 - 55.4 = 1.0 (3.3 ft) Ag 69.60 g/t Pb 4.25% Zn 6.84%

(9.2 ft)
 81.0 - 83.8 = 2.8 m Ag 39.9 g/t
 Pb 2.56% Zn 4.52%

0.0 - 3.3 = 3.3 m (11 ft) Ag 59.31 g/t Pb 3.65% Zn 8.15%

6.1 - 9.8 m = 3.7 m (12.4 ft)
 Ag 93.43 g/t
 Pb 5.15%
 Zn 14.78%

0.0 - 9.8 = 9.8 m (32 ft)
 Ag 55.25 g/t
 Pb 3.69%
 Zn 8.32%

54.4 - 55.4 = 1.0 m (3.3 ft) Ag 69.60 g/t Pb 4.25% Zn 6.84%

81.0 - 83.8 = (9.2 ft) 2.8 m Ag 39.9 g/t
 Pb 2.56% Zn 4.52%

23.5.76 - 24.5.76

ASSAY NUMBER	SECTION		CORE LENGTH (M)	ASSAYS		
	FROM (M)	TO (M)		grams Ag tonne	Pb %	Zn %
2906	0.0	55.0	55.0	0.00	0.00	0.00
	55.0	56.5	1.5	35.31	1.92	3.23
	56.5	61.0	4.5	0.00	0.00	0.00

End of hole

LATITUDE

10833.25

DIP AT COLLAR - 53° 04'

DEPARTURE

7586.312

BEARING 223° 41' 45"

ELEVATION

1137.839

DEPTH 61.0 m (200 ft)

(E.C.I.)

17.5.76 - 17.5.76

ASSAY NUMBER	SECTION		CORE LENGTH (M)	ASSAYS		
	FROM (M)	TO (M)		Ag. ^{grams} / _{tonne}	Pb %	Zn %
2839	0.0 ✓	1.5 ✓	1.5	124.11 ✓	10.85 ✓	23.68 ✓
2840	1.5 ✓	3.0 ✓	1.5	55.54 ✓	6.33 ✓	9.54 ✓
2841	3.0 ✓	4.6 ✓	1.6	130.97 ✓	5.35 ✓	8.80 ✓
2842	4.6 ✓	6.1 ✓	1.5	29.14 ✓	1.60 ✓	3.40 ✓
2843	6.1 ✓	7.6 ✓	1.5	109.02 ✓	6.51 ✓	16.00 ✓
2844	7.6 ✓	9.1 ✓	1.5	86.74 ✓	5.45 ✓	11.54 ✓
2845	9.1 ✓	10.7 ✓	1.6	89.82 ✓	6.83 ✓	11.02 ✓
2846	10.7 ✓	12.2 ✓	1.5	83.65 ✓	5.80 ✓	5.10 ✓
2847	12.2 ✓	13.7 ✓	1.5	65.48 ✓	4.40 ✓	6.67 ✓
2848	13.7 ✓	15.7 ✓	2.0	121.02 ✓	7.13 ✓	12.16 ✓
2849	15.7 ✓	16.8 ✓	1.1	36.34 ✓	1.78 ✓	2.70 ✓
	16.8 ✓	44.2 ✓	27.4	NOT ASSAYED		
2850	44.2 ✓	45.7 ✓	1.5	79.54 ✓	5.65 ✓	7.90 ✓
	45.7 ✓	50.4 ✓	4.7	NOT ASSAYED		
2851	50.4 ✓	51.8 ✓	1.4	94.62 ✓	6.05 ✓	9.15 ✓
2852	51.8 ✓	53.3 ✓	1.5	100.80 ✓	7.05 ✓	9.15 ✓
2853	53.3 ✓	54.7 ✓	1.4	104.91 ✓	7.15 ✓	9.15 ✓
2854	54.7 ✓	56.2 ✓	1.5	41.48 ✓	2.83 ✓	4.15 ✓
2855	56.2 ✓	57.9 ✓	1.7	85.71 ✓	6.58 ✓	6.88 ✓
2856	57.9 ✓	59.4 ✓	1.5	27.42 ✓	2.73 ✓	2.00 ✓
2857	59.4 ✓	61.0 ✓	1.6	32.22 ✓	2.85 ✓	1.64 ✓
2858	61.0 ✓	62.5 ✓	1.5	79.54 ✓	5.80 ✓	7.26 ✓
2859	62.5 ✓	64.0 ✓	1.5	60.34 ✓	3.69 ✓	7.16 ✓
2860	64.0 ✓	65.5 ✓	1.5	32.22 ✓	1.90 ✓	4.00 ✓

End of hole.

LATITUDE
DEPARTURE
ELEVATION

DIP AT COLLAR
BEARING
DEPTH

65.5 m (215 ft)

0.0 - 15.7 = 15.7 m (51.5 ft)

Ag 90.82 g/t.

Pb 6.06%

Zn 11.37%

44.2 - 45.7 = 1.5 m (5 ft) Ag. 79.54 g/t.

Pb 5.65% Zn 7.90%

50.4 - 65.5 = 15.1 m (50 ft)

Ag 65.52 g/t.

Pb 4.65%

Zn 5.99%

24.5.76 - 25.5.76

ASSAY NUMBER	SECTION	FROM (M)	TO (M)	LENGTH (M)	Ag %	Fe %	g/L
2907	0	1.5	1.5	14.06	0.93	1.78	
2908	1.5	3.0	1.5	13.03	0.69	1.18	
2909	3.0	4.6	1.6	35.31	2.57	4.05	
2910	4.6	6.1	1.5	27.43	1.90	4.45	
2911	6.1	7.6	1.5	23.31	1.59	2.60	
2912	7.6	9.1	1.5	13.03	0.73	0.88	
2913	9.1	10.7	1.6	17.14	1.15	1.13	
2914	10.7	12.2	1.5	24.34	1.45	1.65	
2915	12.2	13.7	1.5	32.23	2.22	3.85	
2916	13.7	15.2	1.5	36.34	2.58	4.50	
2917	15.2	16.8	1.6	38.26	2.35	4.70	
2918	16.8	18.3	1.5	20.23	1.44	2.23	
2919	18.3	19.8	1.5	111.09	9.05	15.37	
2920	19.8	21.3	1.5	147.09	9.91	18.46	
2921	21.3	22.9	1.6	169.37	9.65	20.62	
2922	22.9	24.4	1.5	143.32	8.40	18.55	
2923	24.4	25.9	1.5	154.29	10.59	22.50	
2924	25.9	27.4	1.5	103.89	6.54	12.92	
2925	27.4	29.0	1.6	123.09	8.07	12.36	
2926	29.0	30.5	1.5				NOT ASSAYED
2927	30.5	32.0	1.5	103.89	6.74	8.51	
2928	32.0	38.1	6.1	0.00	0.00	0.00	

End of hole

3.0 - 6.1 = 3.1m (10ft)
 Ag. 21.5 g/L. Fe. 2.95% Zn. 4.24%
 low

13.7 - 32.0 = 18.3m (60ft)

Ag 95.70 g/L
 Pb 6.28%
 Zn 11.25%

DIP AT CORNER
 BEARING
 DEPTH 38.1m (125 ft)



DDH U. 90

18.5.76 - 21.5.76

ASSAY NUMBER	SECTION		CORRE			ASSAYS		
	FROM (M)	TO (M)	gms	Pb	Zn	gms	Pb	Zn
2878	0.0	3.0	117.94	9.37	10.48	137.14	10.20	19.89
2879	3.0	4.6	137.14	10.20	19.89	109.02	6.59	13.58
2874	4.6	6.1	109.02	6.59	13.58	67.54	3.33	7.92
2875	6.1	7.2	67.54	3.33	7.92	145.02	8.32	12.91
2876	7.2	7.6	145.02	8.32	12.91	123.08	9.12	12.60
2877	7.6	9.1	123.08	9.12	12.60	181.37	7.49	11.96
2878	9.1	10.7	181.37	7.49	11.96	154.28	9.34	16.30
2879	10.7	12.2	154.28	9.34	16.30	71.65	3.86	5.00
2870	12.2	13.7	71.65	3.86	5.00	7.20	0.18	0.30
2871	13.7	15.2	7.20	0.18	0.30	129.26	8.49	13.74
2872	15.2	17.0	129.26	8.49	13.74	53.49	2.88	4.50
2873	17.0	18.7	53.49	2.88	4.50	17.14	1.11	1.45
2874	18.7	19.2	17.14	1.11	1.45	61.0	6.1	6.1
2875	19.2	21.0	61.0	6.1	6.1	7.80	0.64	0.48
2876	21.0	23.7	7.80	0.64	0.48	47.31	2.18	1.73
2877	23.7	25.0	47.31	2.18	1.73	139.09	7.17	7.84
2878	25.0	27.4	139.09	7.17	7.84	53.49	4.03	5.30
2879	27.4	29.2	53.49	4.03	5.30	44.23	3.63	4.05

End of hole

LATITUDE
 DEPARTURE
 ELEVATION
 DIP AT CORNER
 BEARING
 DEPTH. 79.2 m (260 ft)

$$0 - 18.7 = 18.7 \text{ m (61.4 ft)}$$

Hg 107.86 g/c.

Pb. 6.8%

Zn. 11.4%

$$73.7 - 79.2 = 5.5 \text{ (18.0 ft)}$$

Hg 48.5 g/c.

Pb 3.28%

Zn. 3.67%

E.C.J.

25.5.76 - 27.5.76

ASSAY NUMBER	SECTION		CORE LENGTH(M)	ASSAYS		
	FROM (M)	TO (M)		Ag ^{gram} tone	Pb (%)	Zn (%)
2927	0.0 ✓	1.5 ✓	1.5	35.31 ✓	1.86 ✓	2.63 ✓
2928	1.5 ✓	3.0 ✓	1.5	50.40 ✓	2.63 ✓	2.35 ✓
2929	3.0 ✓	4.6 ✓	1.6	33.26 ✓	1.73 ✓	3.63 ✓
2930	4.6 ✓	6.1 ✓	1.5	17.14 ✓	0.78 ✓	1.83 ✓
2931	6.1 ✓	7.6 ✓	1.5	44.23 ✓	2.38 ✓	4.85 ✓
2932	7.6 ✓	9.1 ✓	1.5	28.46 ✓	1.42 ✓	2.93 ✓
2933	9.1 ✓	10.7 ✓	1.6	22.29 ✓	1.28 ✓	2.50 ✓
2934	10.7 ✓	12.2 ✓	1.5	32.23 ✓	1.96 ✓	3.00 ✓
2935	12.2 ✓	13.7 ✓	1.5	24.34 ✓	1.61 ✓	2.58 ✓
2936	13.7 ✓	15.2 ✓	1.5	26.40 ✓	1.88 ✓	3.75 ✓
2937	15.2 ✓	16.8 ✓	1.6	12.00 ✓	0.85 ✓	1.93 ✓
2938	16.8 ✓	18.3 ✓	1.5	42.51 ✓	3.13 ✓	4.65 ✓
2939	18.3 ✓	19.8 ✓	1.5	46.59 ✓	3.23 ✓	4.30 ✓
2940	19.8 ✓	22.9 ✓	3.1	24.40 ✓	2.08 ✓	4.88 ✓
2941	22.9 ✓	25.9 ✓	3.0	14.06 ✓	0.98 ✓	1.93 ✓
2942	25.9 ✓	29.0 ✓	3.1	25.37 ✓	1.68 ✓	2.83 ✓
2943	29.0 ✓	30.5 ✓	1.5	35.31 ✓	2.33 ✓	2.50 ✓
2944	30.5 ✓	32.0 ✓	1.5	23.31 ✓	1.65 ✓	0.98 ✓
2945	32.0 ✓	33.5 ✓	1.5	26.40 ✓	1.60 ✓	1.63 ✓
2946	33.5 ✓	35.1 ✓	1.6	17.14 ✓	1.18 ✓	0.98 ✓
2947	35.1 ✓	38.1 ✓	3.0	9.94 ✓	0.75 ✓	1.68 ✓
	38.1 ✓	41.1 ✓	3.0	NOT ASSAYED		
2948	41.1 ✓	42.7 ✓	1.6	23.31 ✓	1.20 ✓	2.13 ✓
	42.7 ✓	60.0 ✓	17.3	NOT ASSAYED		
2949	60.0 ✓	62.5 ✓	2.5	16.11 ✓	0.78 ✓	1.48 ✓
2950	62.5 ✓	64.0 ✓	1.5	50.40 ✓	3.48 ✓	3.70 ✓
2951	64.0 ✓	65.5 ✓	1.5	49.37 ✓	3.08 ✓	6.65 ✓
2952	65.5 ✓	67.1 ✓	1.6	26.40 ✓	1.50 ✓	3.00 ✓
2953	67.1 ✓	68.6 ✓	1.5	26.34 ✓	1.40 ✓	2.23 ✓
2954	68.6 ✓	70.1 ✓	1.5	10.97 ✓	0.73 ✓	1.35 ✓
2955	70.1 ✓	73.2 ✓	3.1	13.03 ✓	1.08 ✓	0.88 ✓
2956	73.2 ✓	76.2 ✓	3.0	13.03 ✓	0.70 ✓	0.98 ✓
2957	76.2 ✓	77.7 ✓	1.5	25.37 ✓	1.53 ✓	2.10 ✓
	77.7 ✓	79.2 ✓	1.5	NOT ASSAYED		

DDH U 91.

Continued on Pages 194 & 195

LATITUDE TN

DIP AT COLLAR

DEPARTURE TSW.

BEARING

ELEVATION

DEPTH

97.5
~~106.6 m~~ (320 ft)

61 - 7.6 = 1.5 m (5 ft) Ag. 44.23 g/t. Pb. 2.38% Zn. 4.85%

16.8 - 22.9 = 6.1 m (20 ft) Ag. 34.30 g/t.

Pb. 2.62%

Zn. 4.68%

62.5 - 65.5 = 3.0 m (10 ft) Ag. 49.89 g/t.

Pb. 3.28% Zn. 5.18%

E.C.J.

ASSAY NUMBER	SECTION		CORE LENGTH	ASSAYS		
	FROM (M)	TO (M)		Ag ^{gram} Tonne	Pb %	Zn %
2958	79.2	80.8	1.6	17.14	0.55	0.75
2959	80.8	82.3	1.5	8.22	0.48	0.93
2960	82.3	83.8	1.5	13.02	1.08	1.75
2961	83.8	85.3	1.5	50.40	4.73	1.26
2962	85.3	86.9	1.6	41.48	3.30	2.86
2963	86.9	88.4	1.5	10.97	1.03	1.30
2964	88.4	89.9	1.5	8.22	0.53	0.63
2965	89.9	91.4	1.5	6.17	0.52	0.68
2966	91.4	93.0	1.6	7.20	0.50	0.60
2967	93.0	94.5	1.5	8.22	0.48	0.68
2968	94.5	96.0	1.5	49.37	2.98	3.55
2969	96.0	97.5	1.5	16.11	0.83	0.68
	97.5	106.6	9.1	0.00	0.00	0.00

End of hole

22.5.76 - 23.5.76

PASSAY NUMBER	SECTION			CORE LENGTH			ASSAYS
	From (m)	To (m)	Length	From (m)	To (m)	Length	
2879	0.0	1.8	1.8	124.12	8.40	16.10	
2880	1.8	3.5	1.7	160.46	9.85	13.27	
2881	3.5	5.0	1.5	122.06	8.70	15.02	
2882	5.0	6.4	1.4	137.14	9.17	15.27	
2883	6.4	7.6	1.2	103.89	7.07	14.51	
2884	7.6	8.8	1.2	127.20	10.75	19.12	
2885	8.8	10.4	1.6	23.31	1.44	7.35	
2886	10.4	11.8	1.4	17.14	1.09	9.37	
2887	11.8	13.8	2.0	32.23	1.55	7.01	
2888	13.8	15.2	1.4	72.69	4.35	10.36	
2889	15.2	16.7	1.5	94.63	7.92	18.25	
2890	16.7	18.3	1.6	114.86	8.78	13.59	
2891	18.3	19.8	1.5	17.14	1.08	5.50	
2892	19.8	21.3	1.5	42.51	3.05	8.31	
2893	21.3	22.9	1.6	17.14	0.89	3.40	
2894	22.9	24.4	1.5	21.26	1.14	3.80	
2895	24.4	25.9	1.5	25.37	1.38	2.93	
2896	25.9	27.6	1.7	62.40	4.50	7.90	
2897	27.6	29.0	1.4	34.29	1.33	2.05	
2898	29.0	30.9	1.9	34.29	1.80	2.23	
2899	30.9	32.8	1.9	36.34	2.23	3.58	
2900	32.8	34.6	1.8	17.14	0.81	0.98	
2901	34.6	36.6	2.0	48.34	3.23	5.65	
2902	36.6	38.1	1.5	54.51	3.42	3.50	
2903	38.1	39.6	1.5	43.54	2.54	3.45	
2904	39.6	41.1	1.5	42.51	3.88	2.85	
2905	41.1	42.7	1.6	26.40	1.85	3.38	
2906	42.7	44.2	1.5	17.14	0.77	1.75	
2907	44.2	45.3	1.1	34.29	1.70	2.78	
2908	45.3	47.5	2.2	29.14	2.18	4.48	
	47.5	73.2	25.7	0.00	0.00	0.00	

End of hole

LATITUDE
 DEPARTURE
 ELEVATION

DIP AT CORNER
 BEARING
 DEPTH 73.2 m

$$0.0 - 21.3 = 21.3 \text{ m (70 ft)}$$

Ag 85.39 g/t.

Pb 5.92%

Zn 12.31%

$$25.9 - 27.6 = 1.7 \text{ m (5.6 ft)} \quad \text{Ag. 62.4 g/t. Pb 4.50\% Zn 7.90\%}$$

$$34.6 - 39.6 = 5.0 \text{ m (16.4 ft)} \quad \text{Ag 48.71 g/t.}$$

Pb 3.08%

Zn 4.34%

End of July

ASSAY NUMBER	SECTION	COPE	FROM (M)	TO (M)	LENGTH (M)	Ag. tonne	gms
2970	0.0	1.5	1.5	1.5	37.37	1.78	2.00
2971	1.5	3.0	3.0	1.5	35.31	1.82	2.78
2972	3.0	4.6	4.6	1.6	50.40	2.60	4.55
2973	4.6	4.6	4.6	3.0	45.26	2.55	3.58
2974	7.6	9.1	9.1	1.5	45.26	2.45	3.90
2975	9.1	10.7	10.7	1.6	53.49	2.90	3.80
2976	10.7	12.2	12.2	1.5	37.87	2.10	4.40
2977	12.2	13.7	13.7	1.5	29.14	1.95	2.80
2978	13.7	15.2	15.2	1.5	10.97	1.28	2.93
2979	15.2	16.8	16.8	1.6	15.09	1.13	3.25
2980	16.8	18.3	18.3	1.5	20.23	1.05	2.33
2981	18.3	19.8	19.8	1.5	23.31	1.65	2.88
2982	19.8	21.3	21.3	1.5	22.29	1.68	2.38
2983	21.3	22.9	22.9	1.6	33.26	2.05	3.32
2984	22.9	24.4	24.4	1.5	16.11	1.13	1.08
2985	24.4	25.9	25.9	1.5	24.34	1.35	1.73
2986	25.9	27.4	27.4	1.5	26.40	1.90	2.15
2987	27.4	29.0	29.0	1.6	10.97	0.68	0.70
2988	43.9	45.7	45.7	1.8	47.31	2.85	6.31
2989	45.7	47.2	47.2	1.5	28.46	2.08	3.50
2990	47.2	48.8	48.8	1.6	28.46	2.00	3.80
2991	48.8	50.3	50.3	1.5	23.31	1.48	3.38
2992	50.3	51.8	51.8	1.5	18.17	1.13	2.53
2993	51.8	53.3	53.3	1.5	14.06	0.68	1.50
2994	53.3	54.9	54.9	1.6	17.14	0.98	2.08
2995	54.9	57.9	57.9	3.0	13.03	0.88	1.05
2996	57.9	59.4	59.4	1.5	35.31	2.98	1.85
2997	59.4	61.0	61.0	1.6	29.14	1.78	4.10
2998	61.0	62.5	62.5	1.5	24.34	0.63	2.03
2999	62.5	64.0	64.0	1.5	44.23	2.68	5.45
3000	64.0	65.5	65.5	1.5	56.57	3.38	6.11
3001	65.5	67.1	67.1	1.6	104.92	6.86	12.32
3102	67.1	68.0	68.0	0.9	74.74	4.62	9.59
	68.0	69.5	69.5	1.5	74.74	4.62	9.59
	69.5	76.2	76.2	6.7	0.00	0.00	0.00

29.0 / 43.9 / 14.9 No.1 ASSAYED

67.1 / 68.0 / 0.9 No.1 ASSAYED

LATITUDE

DIP AT COLLAR

DEPARTURE 78W

BEARING

ELEVATION

DEPTH

16.2 m (250 ft)

30-4.6 = 1.6 m (5.25 ft) Ag. 50.4 g/t, Pb. 2.60%
Zn 4.55%

3.0 - 12.2 = 9.2 m (30 ft)

Ag. 46.3 g/t. Pb 2.52%

Zn. 3.97%

LOW

43.9 - 45.7 = 1.8 m (6.0 ft) Ag. 47.3 g/t.

Pb. 2.85% Zn 6.31%

62.5 - 69.5 = 7.0 m (23.0 ft)

Ag 61.6 g/t.

Pb 3.86%

Zn. 7.35%