

Book 2

GRUM PROJECT.  
UNDERGROUND  
D. DRIBLING

° ASSAYS & INTERSECTIONS. °

° U 94 - U 189 °

014940

(E.C.I.)

23.5.76 - 24.5.76

ASSAY NUMBER	SECTION		CORE LENGTH	ASSAYS		
	FROM	TO		Ag g/t.	Pb%	Zn%
3009	0.0 ✓	1.7 ✓	1.7	62.40 ✓	4.35 ✓	7.44 ✓
	1.7 ✓	2.7 ✓	1.0	NOT ASSAYED		
3010	2.7 ✓	5.1 ✓	2.4	24.34 ✓	1.48 ✓	4.43 ✓
	5.1 ✓	6.1 ✓	1.0	NOT ASSAYED		
3011	6.1 ✓	7.6 ✓	1.5	5.14 ✓	0.28 ✓	1.05 ✓
3012	7.6 ✓	9.1 ✓	1.5	7.20 ✓	0.43 ✓	1.05 ✓
3013	9.1 ✓	10.7 ✓	1.6	5.14 ✓	0.33 ✓	0.63 ✓
3014	10.7 ✓	13.9 ✓	3.2	10.97 ✓	0.55 ✓	0.60 ✓
	13.9 ✓	14.7 ✓	0.8	NOT ASSAYED		
3015	14.7 ✓	16.8 ✓	2.1	13.03 ✓	0.68 ✓	0.98 ✓
3016	16.8 ✓	18.3 ✓	1.5	5.14 ✓	0.23 ✓	0.38 ✓
3017	18.3 ✓	20.1 ✓	1.8	16.11 ✓	1.05 ✓	0.75 ✓
3018	20.1 ✓	21.6 ✓	1.5	7.20 ✓	0.35 ✓	0.59 ✓
3019	21.6 ✓	23.3 ✓	1.7	5.14 ✓	0.35 ✓	0.34 ✓
	23.3 ✓	24.6 ✓	1.3	NOT ASSAYED		
3020	24.6 ✓	26.2 ✓	1.6	10.97 ✓	0.73 ✓	0.60 ✓

End of Hole

LATITUDE  
DEPARTURE  
ELEVATION

DIP AT COLLAR  
BEARING  
DEPTH 26.2 m (86 ft).

0.0 - 1.7 = 1.7m (5.6ft) Ag. 62.4 g/t.  
Pb. 4.35% Zn 7.44%

ASSAY SECTION COKE

NUMBER FROM % LENGTH Ag g/c Pb% Zn%

3103 0.0 ✓ 1.5 ✓ 57.60 3.28 6.14 ✓

3104 1.5 ✓ 3.0 ✓ 73.71 4.63 3.85 ✓

3105 3.0 ✓ 4.6 ✓ 41.49 2.45 5.35 ✓

3106 4.6 ✓ 6.7 ✓ 54.51 3.50 5.90 ✓

3107 6.7 ✓ 9.1 ✓ 40.46 2.20 4.97 ✓

3108 9.1 ✓ 10.7 ✓ 33.26 2.93 4.28 ✓

3109 10.7 ✓ 12.2 ✓ 22.23 2.15 3.60 ✓

3110 12.2 ✓ 13.7 ✓ 13.71 4.50 8.41 ✓

3111 13.7 ✓ 15.2 ✓ 70.63 4.05 6.14 ✓

3112 15.2 ✓ 16.8 ✓ 34.29 1.96 3.35 ✓

3113 16.8 ✓ 18.3 ✓ 26.40 1.28 2.95 ✓

3114 18.3 ✓ 19.8 ✓ 46.29 2.80 4.55 ✓

3115 19.8 ✓ 21.3 ✓ 88.80 6.92 9.48 ✓

3116 21.3 ✓ 22.9 ✓ 90.86 6.55 5.90 ✓

3117 22.9 ✓ 24.4 ✓ 55.54 5.40 10.22 ✓

3118 24.4 ✓ 25.5 ✓ 65.49 3.55 11.25 ✓

3119 25.5 ✓ 27.1 ✓ 26.40 1.43 3.53 ✓

3120 27.1 ✓ 28.6 ✓ 31.20 1.98 7.16 ✓

3121 28.6 ✓ 30.2 ✓ 87.77 6.10 13.70 ✓

3122 30.2 ✓ 31.8 ✓ 93.94 6.45 11.70 ✓

3123 31.8 ✓ 33.4 ✓ 78.86 5.96 8.36 ✓

3124 33.4 ✓ 35.0 ✓ 50.40 3.55 4.20 ✓

3125 35.0 ✓ 36.6 ✓ 38.40 2.88 2.65 ✓

3126 36.6 ✓ 38.2 ✓ 52.46 3.35 5.40 ✓

3127 38.2 ✓ 39.8 ✓ 30.17 2.13 2.60 ✓

3128 39.8 ✓ 41.4 ✓ 112.8 1.08 1.38 ✓

3129 41.4 ✓ 43.0 ✓ 66.51 3.85 6.67 ✓

3130 43.0 ✓ 44.6 ✓ 74.74 7.00 8.23 ✓

3131 44.6 ✓ 46.2 ✓ 92.92 5.19 4.70 ✓

3132 46.2 ✓ 47.8 ✓ 119.5 2.2 2.4 ✓

3133 47.8 ✓ 49.4 ✓ 117.3 119.5 117.3 ✓

3134 49.4 ✓ 51.0 ✓ 115.8 117.3 115.8 ✓

3135 51.0 ✓ 52.6 ✓ 114.3 115.8 114.3 ✓

3136 52.6 ✓ 54.2 ✓ 112.8 114.3 112.8 ✓

3137 54.2 ✓ 55.8 ✓ 110.5 112.8 110.5 ✓

3138 55.8 ✓ 57.4 ✓ 108.3 110.5 108.3 ✓

3139 57.4 ✓ 59.0 ✓ 106.1 108.3 106.1 ✓

3140 59.0 ✓ 60.6 ✓ 103.9 106.1 103.9 ✓

3141 60.6 ✓ 62.2 ✓ 101.7 103.9 101.7 ✓

3142 62.2 ✓ 63.8 ✓ 99.5 101.7 99.5 ✓

3143 63.8 ✓ 65.4 ✓ 97.3 99.5 97.3 ✓

3144 65.4 ✓ 67.0 ✓ 95.1 97.3 95.1 ✓

3145 67.0 ✓ 68.6 ✓ 92.9 95.1 92.9 ✓

LATITUDE 7N

DIP AT COLLAR

DEPARTURE 78W

BEARING.

ELEVATION

DEPTH 121.9 m (400 ft).

0.0 - 30.9 = 30.9 m (101.38 ft)

Ag. 49.67 g/t.

Pb 3.23%

Zn 5.74%

38.2 - 47.2 = 9.0 m (29.5 ft)

Ag 72.93 g/t.

Pb 5.09%

Zn 9.03%

50.3 - 53.6 = 3.3 m (10.8 ft) Ag 40.30

LOW.

Pb 2.63% Zn 3.87%

114.3 - 119.5 = 5.2 m (17.0 ft)

Ag 80.06 g/t. Pb 5.33%

Zn 6.30%

24.5.76 - 26.5.76

ASSAY NUMBER	SECTION		CORE LENGTH	ASSAYS		
	FROM	TO		Ag g/t.	Pb%	Zn%
3021	0.0 ✓	1.5 ✓	1.5	53.49 ✓	2.90 ✓	8.50 ✓
3022	1.5 ✓	3.0 ✓	1.5	129.26 ✓	6.26 ✓	11.49 ✓
3023	3.0 ✓	4.6 ✓	1.6	47.31 ✓	4.80 ✓	14.44 ✓
3024	4.6 ✓	6.1 ✓	1.5	60.34 ✓	5.73 ✓	16.23 ✓
3025	6.1 ✓	7.4 ✓	1.3	63.43 ✓	4.45 ✓	12.05 ✓
3026	7.4 ✓	9.3 ✓	1.9	135.09 ✓	10.01 ✓	18.35 ✓
3027	9.3 ✓	10.7 ✓	1.4	103.89 ✓	6.94 ✓	14.60 ✓
3028	10.7 ✓	12.2 ✓	1.5	105.94 ✓	7.19 ✓	14.61 ✓
3029	12.2 ✓	13.7 ✓	1.5	91.89 ✓	6.70 ✓	10.20 ✓
3030	13.7 ✓	15.2 ✓	1.5	73.71 ✓	5.00 ✓	11.17 ✓
3031	15.2 ✓	16.7 ✓	1.5	80.57 ✓	5.46 ✓	11.15 ✓
3032	16.7 ✓	18.7 ✓	2.0	14.06 ✓	0.59 ✓	4.40 ✓
3033	18.7 ✓	19.8 ✓	1.1	39.43 ✓	2.20 ✓	4.30 ✓
3034	19.8 ✓	21.7 ✓	1.9	23.31 ✓	1.18 ✓	2.28 ✓
3035	21.7 ✓	22.9 ✓	1.2	13.03 ✓	0.66 ✓	1.68 ✓
3036	22.9 ✓	24.4 ✓	1.5	9.94 ✓	0.58 ✓	0.90 ✓
3037	24.4 ✓	25.9 ✓	1.5	16.11 ✓	1.10 ✓	2.58 ✓
3038	25.9 ✓	27.4 ✓	1.5	56.57 ✓	3.70 ✓	7.15 ✓
3039	27.4 ✓	29.0 ✓	1.6	42.51 ✓	3.13 ✓	3.55 ✓
3040	29.0 ✓	30.5 ✓	1.5	43.54 ✓	3.40 ✓	3.35 ✓
3041	30.5 ✓	32.0 ✓	1.5	32.23 ✓	1.43 ✓	1.80 ✓
3042	32.0 ✓	33.5 ✓	1.5	16.11 ✓	1.10 ✓	3.80 ✓
3043	33.5 ✓	35.3 ✓	1.8	23.31 ✓	1.80 ✓	3.38 ✓
3044	35.3 ✓	36.2 ✓	0.9	3.09 ✓	0.23 ✓	3.50 ✓
3045	36.2 ✓	38.1 ✓	1.9	40.46 ✓	2.78 ✓	5.50 ✓
3046	38.1 ✓	39.6 ✓	1.5	39.43 ✓	2.53 ✓	5.67 ✓
3047	39.6 ✓	41.1 ✓	1.5	12.00 ✓	0.68 ✓	0.60 ✓
3048	41.1 ✓	42.7 ✓	1.6	15.09 ✓	0.95 ✓	1.75 ✓
3049	42.7 ✓	44.2 ✓	1.5	73.71 ✓	3.23 ✓	4.15 ✓
3050	44.2 ✓	45.7 ✓	1.5	64.46 ✓	2.83 ✓	4.12 ✓
3051	45.7 ✓	47.2 ✓	1.5	TR ✓	0.05 ✓	0.13 ✓
3052	47.2 ✓	48.8 ✓	1.6	27.43 ✓	1.48 ✓	2.80 ✓
3053	48.8 ✓	50.3 ✓	1.5	14.06 ✓	0.73 ✓	1.93 ✓
	50.3 ✓	56.4 ✓	6.1	NOT ASSAYED		
3054	56.4 ✓	57.9 ✓	1.5	7.20 ✓	0.50 ✓	1.25 ✓
	57.9 ✓	98.1 ✓	40.2	NOT ASSAYED		
3055	98.1 ✓	99.9 ✓	1.8	48.34 ✓	3.45 ✓	4.70 ✓
3056	99.9 ✓	101.4 ✓	1.5	116.92 ✓	8.84 ✓	20.27 ✓
3057	101.4 ✓	102.7 ✓	1.3	95.66 ✓	6.41 ✓	15.49 ✓
3058	102.7 ✓	104.4 ✓	1.7	98.74 ✓	7.20 ✓	13.54 ✓

LATITUDE  
DEPARTURE  
ELEVATION

DIP AT CONWAR  
BEARING.  
DEPTH 121.9 m (400 ft)

0.0 - 19.8 = 19.8 m (65 ft)

Ag 77.00 g/t  
Pb 5.29 %  
Zn 11.75 %

25.9 - 30.5 = 4.6 m (15 ft) Ag 47.43 g/t.

Pb 3.40 %  
Zn 4.66 %

36.2 - 39.6 = 3.4 m (11.2 ft) Ag 40.01 g/t.

Pb 2.67 % Zn 5.58 %

42.7 - 45.3 = 2.6 m (8.5 ft) Ag 69.09 g/t

Pb 3.03 % Zn 4.14 %



98.1 - 104.4 = 6.3 m (20.7 ft)

Ag 88.03 g/t  
Pb 6.51 %  
Zn 13.02 %

CONT'D

← 104.4 - 121.9 17.5 0.00 0.00 0.00

3.6.76 - 5.6.76

E.C.J.

ASSAY NUMBER	SECTION		CORE LENGTH	ASSAYS		
	FROM	TO		Ag g/t	Pb%	Zn%
3133	0.0 ✓	3.0 ✓	3.0	51.43 ✓	3.03 ✓	5.65 ✓
3134	3.0 ✓	4.6 ✓	1.6	50.40 ✓	2.93 ✓	4.60 ✓
3135	4.6 ✓	6.1 ✓	1.5	39.43 ✓	2.20 ✓	2.75 ✓
3136	6.1 ✓	7.6 ✓	1.5	46.29 ✓	2.43 ✓	4.90 ✓
3137	7.6 ✓	9.1 ✓	1.5	34.29 ✓	1.73 ✓	4.03 ✓
3138	9.1 ✓	10.7 ✓	1.6	21.26 ✓	1.13 ✓	3.03 ✓
3139	10.7 ✓	12.2 ✓	1.5	27.43 ✓	1.58 ✓	2.98 ✓
3140	12.2 ✓	13.7 ✓	1.5	26.40 ✓	1.53 ✓	4.65 ✓
3141	13.7 ✓	15.2 ✓	1.5	24.34 ✓	1.28 ✓	4.78 ✓
3142	15.2 ✓	16.8 ✓	1.6	28.46 ✓	1.43 ✓	5.47 ✓
3143	16.8 ✓	18.3 ✓	1.5	55.54 ✓	2.98 ✓	4.35 ✓
3144	18.3 ✓	21.3 ✓	3.0	40.46 ✓	2.23 ✓	8.02 ✓
3145	21.3 ✓	22.9 ✓	1.6	28.46 ✓	1.65 ✓	5.15 ✓
3146	22.9 ✓	24.4 ✓	1.5	39.43 ✓	1.68 ✓	5.07 ✓
3147	24.4 ✓	25.9 ✓	1.5	37.37 ✓	1.75 ✓	4.50 ✓
3148	25.9 ✓	27.4 ✓	1.5	44.23 ✓	1.85 ✓	5.08 ✓
3149	27.4 ✓	29.0 ✓	1.6	46.29 ✓	1.98 ✓	4.05 ✓
3150	29.0 ✓	30.5 ✓	1.5	52.46 ✓	2.13 ✓	3.40 ✓
3151	30.5 ✓	32.0 ✓	1.5	42.51 ✓	1.83 ✓	4.90 ✓
3152	32.0 ✓	33.5 ✓	1.5	56.57 ✓	2.81 ✓	4.65 ✓
3153	33.5 ✓	35.1 ✓	1.6	69.60 ✓	3.78 ✓	6.55 ✓
3154	35.1 ✓	36.6 ✓	1.5	33.26 ✓	1.63 ✓	4.84 ✓
3155	36.6 ✓	38.1 ✓	1.5	62.40 ✓	3.35 ✓	8.20 ✓
3156	38.1 ✓	39.6 ✓	1.5	64.46 ✓	3.23 ✓	7.65 ✓
3157	39.6 ✓	40.8 ✓	1.2	66.51 ✓	3.58 ✓	7.13 ✓
3158	40.8 ✓	42.0 ✓	1.2	74.74 ✓	3.80 ✓	8.95 ✓
3159	42.0 ✓	44.2 ✓	2.2	43.54 ✓	3.13 ✓	10.48 ✓
3160	44.2 ✓	45.7 ✓	1.5	58.63 ✓	3.58 ✓	7.85 ✓
3161	45.7 ✓	47.2 ✓	1.5	20.23 ✓	1.30 ✓	2.88 ✓
3162	47.2 ✓	49.3 ✓	2.1	20.23 ✓	1.15 ✓	2.80 ✓
	49.3 ✓	62.5 ✓	13.2	0.00	0.00	0.00

LATITUDE  
DEPARTURE  
ELEVATION

DIP AT COLLAR  
BEARING  
LENGTH 62.5m

0.0 - 45.7 = 45.7m (150 ft)

Ag 44.90 g/t.

Pb 2.37%

Zn 5.61%

27.5.76 - 29.5.76

ASSAY NUMBER	SECTION		CORE LENGTH	ASSAYS		
	FROM	TO		Ag g/t	Pb %	Zn %
3059	0.0 ✓	2.0 ✓	2.0	70.6 ✓	4.75 ✓	8.61 ✓
3060	2.0 ✓	3.8 ✓	1.8	145.0 ✓	8.37 ✓	19.67 ✓
3061	3.8 ✓	5.8 ✓	2.0	152.2 ✓	9.17 ✓	23.91 ✓
3062	5.8 ✓	8.1 ✓	2.3	43.5 ✓	2.10 ✓	4.65 ✓
3063	8.1 ✓	10.2 ✓	2.1	121.0 ✓	7.02 ✓	9.74 ✓
3064	10.2 ✓	12.6 ✓	2.4	76.8 ✓	5.46 ✓	11.55 ✓
3065	12.6 ✓	14.2 ✓	1.6	46.3 ✓	3.10 ✓	4.05 ✓
3066	14.2 ✓	15.6 ✓	1.4	94.6 ✓	5.26 ✓	7.44 ✓
3067	15.6 ✓	17.1 ✓	1.5	45.3 ✓	2.68 ✓	4.70 ✓
3068	17.1 ✓	18.3 ✓	1.2	14.1 ✓	1.13 ✓	1.78 ✓
	18.3 ✓	21.5 ✓	3.2	NOT ASSAYED		
3069	21.5 ✓	22.9 ✓	1.4	9.94 ✓	0.68 ✓	1.30 ✓
3070	22.9 ✓	24.4 ✓	1.5	18.17 ✓	0.73 ✓	0.75 ✓
3071	24.4 ✓	25.9 ✓	1.5	29.14 ✓	1.80 ✓	2.80 ✓
3072	25.9 ✓	27.4 ✓	1.5	46.29 ✓	3.78 ✓	7.05 ✓
	27.4 ✓	63.8 ✓	36.4	0.00	0.00	0.00

LATITUDE  
DEPARTURE  
ELEVATION

DIP AT COLLAR.  
BEARING.  
DEPTH: 63.8 m (209 ft)

0.0 - 17.1 = 17.1m (56 ft)

Ag 88.86 g/t  
Pb 5.48 %  
Zn 10.72 %

25.9 - 27.4 = 1.5m (5 ft) Ag 46.29 g/t

Pb 3.78 % Zn 7.05 %

E.C.J.

6.6.76 - 15.6.76

ASSAY NUMBER	SECTION		CORE LENGTH	ASSAYS		
	FROM	TO		Ag g/t	Pb %	Zn %
3301	0.0 ✓	1.5 ✓	1.5	68.57 ✓	5.81 ✓	6.40 ✓
3302	1.5 ✓	3.0 ✓	1.5	63.43 ✓	4.18 ✓	9.07 ✓
3303	3.0 ✓	4.6 ✓	1.6	78.86 ✓	4.90 ✓	12.40 ✓
3304	4.6 ✓	6.1 ✓	1.5	83.66 ✓	3.00 ✓	8.22 ✓
3305	6.1 ✓	7.6 ✓	1.5	43.54 ✓	2.60 ✓	6.27 ✓
← 106.7 NOT ASSAYED →						
3307	114.3 ✓	115.8 ✓	1.5	108.00 ✓	6.20 ✓	11.25 ✓
3308	115.8 ✓	117.3 ✓	1.5	55.54 ✓	4.30 ✓	6.93 ✓
3309	117.3 ✓	119.7 ✓	2.4	104.92 ✓	6.47 ✓	9.15 ✓
3310	119.7 ✓	121.0 ✓	1.3	80.57 ✓	6.16 ✓	8.77 ✓
3311	121.0 ✓	123.4 ✓	2.4	44.23 ✓	3.10 ✓	4.50 ✓
3312	123.4 ✓	125.0 ✓	1.6	39.43 ✓	2.98 ✓	4.35 ✓
3313	125.0 ✓	126.5 ✓	1.5	10.97 ✓	0.85 ✓	1.38 ✓
126.5 132.9 6.4 NOT ASSAYED						
3314	132.9 ✓	135.6 ✓	2.7	15.09 ✓	0.55 ✓	0.63 ✓
3315	135.6 ✓	139.5 ✓	3.9	8.91 ✓	0.38 ✓	0.58 ✓
3316	139.5 ✓	143.3 ✓	2.8	8.91 ✓	0.35 ✓	0.38 ✓
3317	143.3 ✓	145.3 ✓	3.0	7.20 ✓	0.18 ✓	0.60 ✓
3318	145.3 ✓	147.0 ✓	1.7	7.20 ✓	0.23 ✓	0.60 ✓
3319	147.0 ✓	148.7 ✓	1.7	13.03 ✓	0.28 ✓	0.43 ✓
148.7 150.3 1.6 NOT ASSAYED						
3320	150.3 ✓	153.3 ✓	3.0	49.37 ✓	3.00 ✓	3.75 ✓
	153.3 ✓	192.9 ✓	29.6	0.00	0.00	0.00

LATITUDE  
DEPARTURE  
ELEVATION

DIP AT COLLAR  
BEARING  
DEPTH. 182.9m (600 ft)

0.0 - 7.6 = 7.6m (25 ft)  
Ag 67.76 g/t.  
Pb 4.11%  
Zn 8.52%

From	To	Length	Ag	Pb	Zn
7.6 ✓	49.2 ✓	41.6	0.00	0.00	0.00
49.2 ✓	50.6 ✓	1.4	62.40	4.09	5.78
50.6 ✓	114.3 ✓	63.7	0.00	0.00	0.00

114.3 - 125.0 = 10.7m (35 ft)  
Ag 72.07 g/t.  
Pb 4.81%  
Zn 7.33%

150.3 - 153.3 = 3.0m (10.0 ft)  
Ag 49.37 g/t. Pb 3.00%  
Zn 3.75%

Completed

(Note - included above)

3306. 49.2 50.6 1.4 62.40 4.09 5.78

?

14  
E.C.J.

DDH U 100 ✓

29.5.76 - 3.6.76

ASSAY NUMBER	SECTION		CORE LENGTH	ASSAYS		
	FROM	TO		Ag g/t	Pb%	Zn%
3075	0.0 ✓	3.0 ✓	3.0	96.69 ✓	5.75 ✓	11.65 ✓
3076	3.0 ✓	4.6 ✓	1.6	111.09 ✓	7.70 ✓	14.97 ✓
3077	4.6 ✓	6.1 ✓	1.5	164.57 ✓	11.77 ✓	21.01 ✓
3078	6.1 ✓	7.6 ✓	1.5	127.20 ✓	9.26 ✓	16.97 ✓
3079	7.6 ✓	9.1 ✓	1.5	90.86 ✓	7.30 ✓	13.60 ✓
3080	9.1 ✓	10.7 ✓	1.6	92.92 ✓	6.75 ✓	13.13 ✓
3081	10.7 ✓	12.2 ✓	1.5	37.37 ✓	2.85 ✓	6.01 ✓
3082	12.2 ✓	13.7 ✓	1.5	78.86 ✓	6.15 ✓	10.53 ✓
3083	13.7 ✓	15.2 ✓	1.5	33.26 ✓	2.00 ✓	4.24 ✓
3084	15.2 ✓	16.8 ✓	1.6	23.31 ✓	1.03 ✓	3.50 ✓
3085	16.8 ✓	18.3 ✓	1.5	33.26 ✓	1.73 ✓	4.38 ✓
3086	18.3 ✓	19.8 ✓	1.5	68.57 ✓	4.74 ✓	10.17 ✓
3087	19.8 ✓	21.3 ✓	1.5	52.46 ✓	3.78 ✓	4.10 ✓
3088	21.3 ✓	22.9 ✓	1.6	17.14 ✓	1.23 ✓	1.88 ✓
3089	22.9 ✓	24.4 ✓	1.5	33.26 ✓	2.50 ✓	3.05 ✓
3090	24.4 ✓	25.9 ✓	1.5	36.34 ✓	2.78 ✓	4.55 ✓
3091	25.9 ✓	26.7 ✓	0.8	25.37 ✓	1.63 ✓	2.88 ✓
3092	26.7 ✓	27.4 ✓	0.7	30.17 ✓	2.18 ✓	5.93 ✓
3093	27.4 ✓	29.8 ✓	2.4	19.20 ✓	1.23 ✓	2.73 ✓
3094	29.8 ✓	31.5 ✓	1.7	50.40 ✓	3.14 ✓	5.60 ✓
3095	31.5 ✓	33.5 ✓	2.0	40.46 ✓	2.83 ✓	6.49 ✓
3096	33.5 ✓	35.1 ✓	1.6	17.14 ✓	1.38 ✓	2.55 ✓
3097	35.1 ✓	36.6 ✓	1.5	34.29 ✓	2.38 ✓	5.90 ✓
3098	36.6 ✓	38.1 ✓	1.5	17.14 ✓	1.13 ✓	4.94 ✓
3099	38.1 ✓	39.6 ✓	1.5	41.49 ✓	3.08 ✓	3.50 ✓
3100	39.6 ✓	41.1 ✓	1.5	25.37 ✓	1.70 ✓	7.00 ✓
3201	41.1 ✓	42.7 ✓	1.6	15.09 ✓	1.05 ✓	2.63 ✓
3202	42.7 ✓	44.2 ✓	1.5	86.74 ✓	4.89 ✓	10.94 ✓
3203	44.2 ✓	47.2 ✓	3.0	37.37 ✓	2.43 ✓	3.15 ✓
3204	47.2 ✓	48.8 ✓	1.6	71.66 ✓	4.89 ✓	2.75 ✓
3205	48.8 ✓	50.3 ✓	1.5	72.69 ✓	5.54 ✓	4.50 ✓
3206	50.3 ✓	51.8 ✓	1.5	26.40 ✓	1.90 ✓	1.83 ✓
3207	51.8 ✓	54.0 ✓	2.2	18.17 ✓	1.43 ✓	0.68 ✓
3208	54.0 ✓	56.5 ✓	2.5	TR ✓	TR ✓	0.13 ✓
3209	56.5 ✓	58.7 ✓	2.2	15.09 ✓	1.10 ✓	2.45 ✓
	58.7 ✓	80.2 ✓	21.5	NO ASSAYED		

DDH U 100 Continued on  
Pages 16 & 17.

MAGNITUDE  
DEPARTURE  
ELEVATION

BIP AT CONWAR  
BEARING.  
DEPTH. 121.9 m (400 ft).

0.0 - 50.3 = 50.3 m (165 ft)

Ag 54.25 g/t.

Pb 3.78 %

Zn 6.94 %

E.C.J.

ASSAY NUMBER	SECTION		CORE LENGTH	ASSAYS		
	FROM	TO		Ag g/t	Pb%	Zn%
3210	80.2	82.0	1.8	31.20	2.20	5.20
3211	82.0	83.2	1.2	22.29	1.38	3.70
3212	83.2	86.4	3.2	7.20	0.48	1.23
3213	86.4	89.4	3.0	7.20	0.55	1.53
3214	89.4	90.4	1.0	45.26	3.28	5.50
3215	90.4	92.2	1.8	47.31	3.43	6.97
	92.2	121.9	29.7	0.00	0.00	0.00

LATITUDE LN

DEPARTURE Tow

ELEVATION

DIP AT COLLAR

BEARING.

DEPTH.

80.2 - 82.0 = 1.8 m (5.9 ft) Ag. 31.20 g/t  
Pb. 2.20% Zn 5.20%

89.4 - 92.2 = 2.8 m (9.2 ft) Ag. 46.58  
Pb. 3.38% Zn. 6.45%

E.C.J.

16.6.76 - 21.6.76

ASSAY NUMBER	SECTION		CORE LENGTH	ASSAYS		
	FROM	TO		Ag g/c	Pb %	Zn %
3321	0.0 ✓	2.7 ✓	2.7	74.74 ✓	4.98 ✓	7.46 ✓
3322	2.7 ✓	4.2 ✓	1.5	46.29 ✓	2.88 ✓	5.40 ✓
	4.2	54.9	50.7	NOT ASSAYED		
3323	54.9 ✓	56.4 ✓	1.5	126.17 ✓	7.77 ✓	13.02 ✓
3324	56.4 ✓	57.9 ✓	1.5	41.49 ✓	2.80 ✓	2.76 ✓
3325	57.9 ✓	59.4 ✓	1.5	49.37 ✓	3.38 ✓	3.06 ✓
3326	59.4 ✓	61.0 ✓	1.6	72.69 ✓	4.65 ✓	3.10 ✓
3327	61.0 ✓	62.5 ✓	1.5	64.46 ✓	4.08 ✓	4.86 ✓
3328	62.5 ✓	64.0 ✓	1.5	50.40 ✓	3.50 ✓	2.80 ✓
3329	64.0 ✓	65.6 ✓	1.6	66.51 ✓	4.35 ✓	5.84 ✓
	65.6	67.3	1.7	NOT ASSAYED		
3330	67.3 ✓	70.1 ✓	2.8	28.46 ✓	1.93 ✓	2.70 ✓
3331	70.1 ✓	71.6 ✓	1.5	40.46 ✓	2.60 ✓	3.66 ✓
3332	71.6 ✓	73.2 ✓	1.6	45.26 ✓	3.08 ✓	2.46 ✓
3333	73.2 ✓	74.7 ✓	1.5	32.23 ✓	2.05 ✓	2.60 ✓
3334	74.7 ✓	77.7 ✓	3.0	3.09 ✓	0.13 ✓	0.60 ✓
3335	77.7 ✓	80.8 ✓	3.1	24.34 ✓	1.48 ✓	3.00 ✓
3336	80.8 ✓	83.8 ✓	3.0	19.20 ✓	1.03 ✓	1.20 ✓
3337	83.8 ✓	86.9 ✓	3.1	20.23 ✓	1.30 ✓	1.88 ✓
3338	86.9 ✓	89.9 ✓	3.0	6.17 ✓	0.33 ✓	0.46 ✓
3339	89.9 ✓	91.4 ✓	1.5	24.34 ✓	1.48 ✓	2.18 ✓
3340	91.4 ✓	93.0 ✓	1.6	31.20 ✓	1.98 ✓	2.80 ✓
3341	93.0 ✓	95.5 ✓	2.5	10.97 ✓	0.85 ✓	0.90 ✓
3342	95.5 ✓	98.1 ✓	2.6	13.03 ✓	1.18 ✓	1.20 ✓
3343	98.1 ✓	99.2 ✓	1.1	130.97 ✓	8.05 ✓	13.43 ✓
	99.2	130.6	31.4	NOT ASSAYED		
3344	130.6 ✓	132.6 ✓	2.0	2.06 ✓	0.05 ✓	0.13 ✓
3345	132.6 ✓	134.1 ✓	1.5	TR ✓	0.02 ✓	0.03 ✓
3346	134.1 ✓	137.2 ✓	3.1	TR ✓	0.03 ✓	0.05 ✓
3347	137.2 ✓	140.2 ✓	3.0	6.17 ✓	0.48 ✓	0.73 ✓
3348	140.2 ✓	141.7 ✓	1.5	3.09 ✓	0.08 ✓	0.18 ✓
3349	141.7 ✓	143.3 ✓	1.6	TR ✓	0.03 ✓	0.13 ✓
3350	143.3 ✓	144.8 ✓	1.5	26.40 ✓	1.60 ✓	2.06 ✓
3351	144.8 ✓	145.9 ✓	1.1	65.49 ✓	4.88 ✓	6.03 ✓
3352	145.9 ✓	147.5 ✓	1.6	72.69 ✓	4.96 ✓	10.11 ✓
3353	147.5 ✓	149.0 ✓	1.5	23.31 ✓	1.53 ✓	2.68 ✓
	149.0 ✓	175.3 ✓	26.3	0.00	0.00	0.00

1.1m (3.6 ft) •

LATITUDE 7N

DEPARTURE 78W

ELEVATION

DIP AT CORNER.

BEARING.

DEPTH 175.3m (575ft)

 $0.0 - 4.2 = 4.2m (13.8ft)$  Ag. 64.58 g/t.

Pb. 4.23% Zn. 6.12%

 $54.9 - 65.6 = 10.7m (35ft)$ 

Ag 67.34 g/t.

Pb 4.36%

Zn 5.05%

 $144.8 - 147.5 = 2.7m (9.0ft)$  Ag. 69.77 g/t

Pb. 4.93% Zn 8.45%

E.C.J.

DDH U 102

3.6.76 - 4.6.76

ASSAY NUMBER	SECTION		CORE LENGTH	ASSAYS		
	FROM	TO		Ag g/t	Pb %	Zn %
3214	0.0	3.0	3.0	114.17	8.08	16.53
3217	3.0	4.6	1.6	128.23	7.74	15.98
3218	4.6	6.1	1.5	112.12	7.67	17.00
3219	6.1	8.1	2.0	127.20	9.90	19.64
3220	8.1	12.0	3.9	12.00	0.95	1.68
3221	12.0	13.7	1.7	74.74	6.15	8.89
3222	13.7	15.2	1.5	46.29	3.05	5.95
3223	15.2	18.3	3.1	35.31	2.80	3.05
3224	18.3	19.8	1.5	87.77	6.97	5.20
3225	19.8	22.2	2.4	TR.	0.05	0.03
3226	22.2	22.7	0.5	145.03	7.72	14.54
3227	22.7	24.4	1.7	13.03	0.55	1.05
3228	24.4	25.9	1.5	13.03	0.88	1.20
3229	25.9	29.0	3.1	44.23	2.58	4.00
3230	29.0	33.5	4.5	35.31	2.58	4.40
	33.5	37.9	4.4	NOT ASSAYED		
3231	37.9	39.6	1.7	27.43	2.48	6.25
3232	39.6	41.1	1.5	34.29	2.33	2.90
3233	41.1	42.7	1.6	43.54	2.98	7.43
3234	42.7	44.2	1.5	50.40	3.78	7.90
3235	44.2	45.7	1.5	40.46	2.98	5.45
	45.7	47.2	1.5	0.00	0.00	0.00

LATITUDE	DEPARTURE	ELEVATION	DIP AT COLLAR	
			BEARING	DEPTH
			47.2 m (155 ft)	
0.0 - 22.7 = 22.7 m (74.5 ft)				
			Ag 67.28 g/t.	
			Pb 4.84%	
			Zn 8.60%	
0.0 - 45.7 = 45.7 m (150 ft)				
			Ag 47.46 g/t.	
			Pb 3.38%	
			Zn 6.05%	
0.0 - 33.5 = 33.5 m (110.0 ft)				
			Ag 55.67 g/t.	
			Pb 3.93%	
			Zn 6.85%	
37.9 - 45.7 = 7.8 m (25.6 ft)				
			Ag 38.97 g/t	
			Pb 2.91%	
			Zn 6.02%	

E.C.J.

21.6.76 - 24.6.76

ASSAY NUMBER	SECTION		CORE LENGTH	ASSAYS		
	FROM	TO		Ag g/t	Pb%	Zn%
3354	0.0 ✓	1.5 ✓	1.5	81.60 ✓	5.56 ✓	8.35 ✓
3355	1.5 ✓	3.0 ✓	1.5	44.46 ✓	4.43 ✓	7.20 ✓
3356	3.0 ✓	4.6 ✓	1.6	42.51 ✓	3.23 ✓	4.45 ✓
	4.6 ✓	129.5 ✓	124.9	0.00	0.00	0.00

LATITUDE IN

DEPARTURE 78W.

ELEVATION

DIP AT COLLAR.

BEARING

DEPTH 129.5 m (425 ft)

0.0 - 4.6 = 4.6 m (15 ft) Ag 62.41 g/t.  
 Pb 4.38%  
 Zn 6.62%

E.C.I.

4.6.76 - 4.6.76

ASSAY NUMBER	SECTION		CORE LENGTH	ASSAYS		
	FROM	TO		Ag g/t	Pb%	Zn%
3236	0.0 ✓	3.0 ✓	3.0	98.74 ✓	7.47 ✓	14.44 ✓
3237	3.0 ✓	4.6 ✓	1.6	120.00 ✓	7.54 ✓	16.69 ✓
3238	4.6 ✓	6.1 ✓	1.5	111.09 ✓	7.68 ✓	18.02 ✓
3239	6.1 ✓	7.6 ✓	1.5	108.00 ✓	7.52 ✓	17.51 ✓
3240	7.6 ✓	9.1 ✓	1.5	166.29 ✓	12.32 ✓	22.41 ✓
3241	9.1 ✓	10.7 ✓	1.6	172.46 ✓	12.25 ✓	22.03 ✓
3242	10.7 ✓	12.2 ✓	1.5	134.06 ✓	10.00 ✓	17.46 ✓
3243	12.2 ✓	13.7 ✓	1.5	166.29 ✓	8.24 ✓	13.98 ✓
	13.7 ✓	31.4 ✓	17.7	0.00	0.00	0.00

LATITUDE 6N

DEPARTURE 10W

ELEVATION

DIP AT COLLAR.

BEARING

LENGTH 31.4 m. (103 ft)

0.0 - 13.7 = 13.7 m (45 ft)
Ag 130.78 g/t.
Pb 8.96%
Zn 17.84%

E.C.I.

27.6.76 - 30.6.76

ASSAY NUMBER	SECTION		CORE LENGTH	ASSAYS		
	FROM	TO		Ag g/t	Pb %	Zn %
3357	0.0 ✓	1.5 ✓	1.5	5.14 ✓	0.15 ✓	0.13 ✓
3358	1.5 ✓	3.0 ✓	1.5	6.17 ✓	0.33 ✓	0.20 ✓
3359	3.0 ✓	5.6 ✓	2.6	22.29 ✓	1.38 ✓	3.23 ✓
	5.6 ✓	38.1 ✓	32.5	0.00	0.00	0.00

LOW ASSAYS

LATITUDE TN

DIP AT COLLAR

DEPARTURE TSW.

BEARING

ELEVATION

DEPTH 38.1 m (125 ft).

DPH U 106

5.6.76 - 9.6.76

ASSAY	SECTION	COKE	FROM	TO	LENGTH	Ag g/c	Pb %	Zn g/c
3244			0.0	1.5	1.5	168.34	9.86	22.57
3245			1.5	3.5	2.0	137.14	8.40	19.86
3246			3.5	4.6	1.1	78.86	4.58	12.62
3247			4.6	6.2	1.6	137.14	8.81	19.97
3248			6.2	9.2	3.0	150.17	9.20	15.20
3249			9.2	10.7	1.5	130.97	9.74	13.95
3250			10.7	13.9	3.2	146.06	9.41	14.72
3251			13.9	15.2	1.3	14.06	0.63	0.48
3252			15.2	16.8	1.6	6.17	0.30	0.45
3253			16.8	17.7	0.9			
3254			17.7	19.1	1.4	78.86	4.98	5.70
3255			19.1	102.1	83.0			
3256			102.1	103.6	1.5	111.09	8.88	10.50
3257			103.6	105.2	1.6	34.29	2.63	5.74
3258			105.2	106.7	1.5	32.23	2.23	4.35
3259			106.7	108.2	1.5	30.17	2.00	3.90
3260			108.2	109.7	1.5	30.17	2.03	3.85
3261			109.7	111.3	1.6	26.40	1.64	3.68
3262			111.3	112.8	1.5	21.26	1.23	2.90
3263			112.8	114.3	1.5	15.09	0.75	1.40
3264			114.3	115.8	1.5	22.29	1.45	2.58
3265			115.8	117.3	1.5	17.14	1.28	3.40
3266			117.3	118.9	1.6	16.11	1.10	2.43
3267			118.9	120.4	1.5	21.26	1.30	3.68
3268			120.4	121.9	1.5	20.23	1.10	2.80
3269			121.9	123.4	1.5	24.34	1.25	4.78
3270			123.4	125.1	1.7	34.29	1.58	5.20
3271			125.1	127.5	2.4			
3272			127.5	129.9	2.4			
3273			129.9	137.2	7.3			

NOT ASSAYED

DEPTH 137.2m (450 ft)

DEPARTURE TOW BEARING

0.0 - 13.9 = 13.9m (45.6 ft)

Ag 140.09 g/c  
Pb 8.85 %  
Zn 16.77 %

100.0 - 106.7 = 6.7m (22.0 ft)

Ag 65.00 g/c  
Pb 4.68 %  
Zn 6.48 %

121.9 - 125.1 = 3.2m (10.5 ft)  
Ag 29.63 g/c  
Pb 1.43 %  
Zn 5.00 %

LOW

DPH U 107

30.6.74 - 25.7.74

ASSAY NUMBER	SECTION	From	%	LENGTH	Ag g/lc	Pb %	g
--------------	---------	------	---	--------	---------	------	---

ASSAYS

DEPARTURE 15M

ELEVATION

DEPTH 70.1 m. (230 ft)

BEARING

DIP AT CORNER

LATITUDE 74

LONGITUDE 74

LONGITUDE 74

LONGITUDE 74

LONGITUDE 74

LONGITUDE 74

LONGITUDE 74

LONGITUDE 74

LONGITUDE 74

LONGITUDE 74

LONGITUDE 74

LONGITUDE 74

LONGITUDE 74

LONGITUDE 74

LONGITUDE 74

LONGITUDE 74

LONGITUDE 74

LONGITUDE 74

LONGITUDE 74

LONGITUDE 74

LONGITUDE 74

LONGITUDE 74

LONGITUDE 74

LONGITUDE 74

LONGITUDE 74

LONGITUDE 74

LONGITUDE 74

LONGITUDE 74

ASSAY NUMBER	SECTION	From	%	LENGTH	Ag g/lc	Pb %	g
--------------	---------	------	---	--------	---------	------	---

ASSAYS

DEPARTURE 15M

ELEVATION

DEPTH 70.1 m. (230 ft)

BEARING

DIP AT CORNER

LATITUDE 74

LONGITUDE 74

LONGITUDE 74

LONGITUDE 74

LONGITUDE 74

LONGITUDE 74

LONGITUDE 74

LONGITUDE 74

LONGITUDE 74

LONGITUDE 74

LONGITUDE 74

LONGITUDE 74

LONGITUDE 74

LONGITUDE 74

LONGITUDE 74

LONGITUDE 74

LONGITUDE 74

LONGITUDE 74

LONGITUDE 74

LONGITUDE 74

LONGITUDE 74

LONGITUDE 74

LONGITUDE 74

LONGITUDE 74

LONGITUDE 74

LONGITUDE 74

LONGITUDE 74

LONGITUDE 74

$Ag - 44.2 = 2.2m (1ft) Ag, 60.34glt$

$Pb, 3.60\% Zn 6.43\%$

$57.5 - 62.5 = 5.0m (16ft)$

$Ag, 55.95glt, Pb 3.47\%$

$Zn 5.62\%$

$Ag 49.13glt, Pb 2.36\%$

$Zn 5.71\%$

$21.3 - 38.6 = 17.3m (57ft)$

$Ag 57.36glt, Pb 4.00\%$

$Zn 6.74\%$

$Ag 44.2 = 2.2m (7.5ft)$

$Pb 2.36\%$

$Zn 5.71\%$

$Ag 49.13glt, Pb 2.36\%$

$Zn 5.71\%$

$Ag 49.13glt, Pb 2.36\%$

$Zn 5.71\%$

$Ag 49.13glt, Pb 2.36\%$

$Zn 5.71\%$

$Ag 49.13glt, Pb 2.36\%$

$Zn 5.71\%$

$Ag 49.13glt, Pb 2.36\%$

$Zn 5.71\%$

$Ag 49.13glt, Pb 2.36\%$

$Zn 5.71\%$

$Ag 49.13glt, Pb 2.36\%$

$Zn 5.71\%$

$Ag 49.13glt, Pb 2.36\%$

$Zn 5.71\%$

$Ag 49.13glt, Pb 2.36\%$

$Zn 5.71\%$

$Ag 49.13glt, Pb 2.36\%$

$Zn 5.71\%$

$Ag 49.13glt, Pb 2.36\%$

$Zn 5.71\%$

$Ag 49.13glt, Pb 2.36\%$

$Zn 5.71\%$

$Ag 49.13glt, Pb 2.36\%$

$Zn 5.71\%$

$Ag 49.13glt, Pb 2.36\%$

$Zn 5.71\%$

$Ag 49.13glt, Pb 2.36\%$



10.6.76 - 12.6.76

ASSAY NUMBER	SECTION		CORE LENGTH	ASSAYS		
	FROM	TO		Ag g/t	Pb %	Zn %
3273	0.0 ✓	3.0 ✓	3.0	144.23	9.31	21.22
3274	3.0 ✓	4.6 ✓	1.6	55.54	3.70	6.91
3275	4.6 ✓	6.1 ✓	1.5	83.66	4.19	6.74
3276	6.1 ✓	7.8 ✓	1.7	85.72	5.98	10.61
3277	7.8 ✓	9.1 ✓	1.3	88.80	6.38	9.64
3278	9.1 ✓	10.7 ✓	1.6	17.14	0.88	1.03
3279	10.7 ✓	12.8 ✓	2.1	17.14	0.83	1.15
	12.8 ✓	53.9 ✓	41.1	NOT ASSAYED		
3280	53.9 ✓	54.9 ✓	1.0	117.60	8.30	9.87
3281	54.9 ✓	56.4 ✓	1.5	111.09	7.85	9.51
3282	56.4 ✓	58.6 ✓	2.2	92.92	6.75	8.44
3283	58.6 ✓	61.0 ✓	2.4	84.69	6.54	8.64
3284	61.0 ✓	62.5 ✓	1.5	34.29	2.73	2.35
3285	62.5 ✓	64.0 ✓	1.5	23.31	1.65	1.50
3286	64.0 ✓	65.5 ✓	1.5	37.37	3.60	2.78
3287	65.5 ✓	67.1 ✓	1.6	20.23	1.80	1.48
3288	67.1 ✓	68.6 ✓	1.5	16.11	1.05	0.60
3289	68.6 ✓	70.1 ✓	1.5	4.11	0.10	0.43
3290	70.1 ✓	72.5 ✓	2.4	10.97	0.43	0.68

LATITUDE  
DEPARTURE  
ELEVATION

DIP AT CORNER  
BEARING  
DEPTH. 12.5 m (238 ft)

0.0 - 9.1 = 9.1 m (30 ft)

Ag 99.8 g/t.  
Pb 6.44%  
Zn 12.68%

53.9 - 61.0 = 7.1 m (23.3 ft)

Ag 97.45 g/t.  
Pb 7.13%  
Zn 8.94%

64.0 - 65.5 = 1.5 m (5 ft) Ag 37.37 g/t. Pb 3.60%. Zn 2.78% | LOW.

E.O.J.

7.7.76 - 14.7.76.

ASSAY NUMBER	SECTION		CORE LENGTH	ASSAYS		
	FROM	TO		Ag g/t	Pb %	Zn %
3369	0.0 ✓	1.5 ✓	1.5	30.17 ✓	1.73 ✓	5.35 ✓
3370	1.5 ✓	3.0 ✓	1.5	34.29 ✓	1.83 ✓	4.48 ✓
3371	3.0 ✓	4.6 ✓	1.6	108.00 ✓	5.62 ✓	11.02 ✓
	4.6 ✓	50.8 ✓	46.2	NOT ASSAYED		
3395	50.8 ✓	53.3 ✓	2.5	10.63 ✓	4.90 ✓	8.12 ✓
	53.3 ✓	67.3 ✓	14.0	NOT ASSAYED		
3396	67.3 ✓	70.1 ✓	2.8	43.54 ✓	2.40 ✓	3.36 ✓
3397	70.1 ✓	71.6 ✓	1.5	50.40 ✓	3.38 ✓	5.64 ✓
3398	71.6 ✓	73.2 ✓	1.6	20.23 ✓	1.60 ✓	3.68 ✓
3399	73.2 ✓	74.7 ✓	1.5	3.09 ✓	0.35 ✓	0.20 ✓
3400	74.7 ✓	76.2 ✓	1.5	37.37 ✓	2.20 ✓	3.66 ✓
3801	76.2 ✓	77.7 ✓	1.5	12.69 ✓	4.55 ✓	8.36 ✓
3802	77.7 ✓	79.2 ✓	1.5	57.60 ✓	3.20 ✓	6.60 ✓
3803	79.2 ✓	81.0 ✓	1.8	8.91 ✓	0.68 ✓	1.18 ✓
	81.0 ✓	90.8 ✓	9.8	NOT ASSAYED		
3804	90.8 ✓	93.0 ✓	2.2	21.26 ✓	1.63 ✓	1.88 ✓
3805	93.0 ✓	94.5 ✓	1.5	33.26 ✓	2.15 ✓	3.30 ✓
3806	94.5 ✓	96.0 ✓	1.5	38.40 ✓	2.43 ✓	4.10 ✓
3807	96.0 ✓	97.5 ✓	1.5	28.11 ✓	1.70 ✓	3.95 ✓
3808	97.5 ✓	99.1 ✓	1.6	9.94 ✓	0.73 ✓	1.15 ✓
3809	99.1 ✓	100.6 ✓	1.5	20.23 ✓	1.55 ✓	2.98 ✓
	100.6 ✓	115.8 ✓	15.2	NOT ASSAYED		
3810	115.8 ✓	116.7 ✓	1.1	31.20 ✓	1.83 ✓	1.85 ✓

LATITUDE 7N  
DEPARTURE 78W  
ELEVATION

DIP AT CORNER  
BEARING  
DEPTH 116.7 m (383 ft).

0.0 - 4.6 m = 4.6 m (15 ft)

Ag. 58.58 g/t. Pb 3.12 %  
Zn. 7.04 %

70.1 - 71.6 = 1.5 m (5.0 ft) Ag. 50.40 g/t. Pb 3.38 % Zn 5.64 %

ECJ

12.6.76 - 13.6.76

ASSAY NUMBER	SECTION		CORE LENGTH (M)	ASSAYS		
	FROM (M)	TO (M)		Ag g/t.	Pb %	Zn %
3291	0.0 ✓ 55.7 ✓	55.7 ✓ 57.9 ✓	55.7 2.2	8.00 ✓ 35.31 ✓	0.00 ✓ 2.25 ✓	0.00 ✓ 3.35 ✓
3292	57.9 ✓	59.4 ✓	1.5	61.37 ✓	3.98 ✓	5.76 ✓
3293	59.4 ✓	61.0 ✓	1.6	40.46 ✓	2.85 ✓	3.35 ✓
3294	61.0 ✓	62.5 ✓	1.5	33.26 ✓	2.53 ✓	2.25 ✓
3295	62.5 ✓	64.0 ✓	1.5	44.23 ✓	2.93 ✓	4.40 ✓
3296	64.0 ✓	65.5 ✓	1.5	50.40 ✓	3.00 ✓	2.30 ✓
3297	65.5 ✓	66.8 ✓	1.3	15.09 ✓	1.58 ✓	3.00 ✓
	66.8 ✓	90.8 ✓	24.0	0.00	0.00	0.00

LATITUDE TN 10894.584

DIP AT COLLAR

DEPARTURE 16W. 7627.339

BEARING

ELEVATION 1132.983

LENGTH. 90.8 m (298 ft)

55.7 - 65.5 = 9.8 m (32 ft)

Ag 43.5 g/t.

LOW

Pb 2.87%

Zn 3.55%

E.C.I.

6.7.76 - 11.7.76

ASSAY NUMBER	SECTION		CORE LENGTH(M)	ASSAYS		
	FROM (M)	TO (M)		Ag g/t	Pb %	Zn %
3372	0.00 ✓ 59.8 ✓	59.8 ✓ 61.3 ✓	59.8 1.5	0.00 67.54 ✓	0.00 6.20 ✓	0.00 6.00 ✓
3373	61.3 ✓	62.8 ✓	1.5	63.43 ✓	5.10 ✓	6.37 ✓
3374	62.8 ✓	64.3 ✓	1.5	31.20 ✓	2.35 ✓	3.46 ✓
3375	64.3 ✓	65.8 ✓	1.5	1.89 ✓	0.40 ✓	0.68 ✓
3376	65.8 ✓	67.3 ✓	1.5	9.94 ✓	0.55 ✓	0.13 ✓
3377	67.3 ✓	68.8 ✓	1.5	5.14 ✓	0.38 ✓	0.35 ✓
3378	68.8 ✓	70.3 ✓	1.5	18.17 ✓	1.70 ✓	2.80 ✓
3379	70.3 ✓	71.8 ✓	1.5	13.03 ✓	0.85 ✓	1.10 ✓
3380	71.8 ✓	73.3 ✓	1.5	6.17 ✓	0.28 ✓	0.43 ✓
3381	73.3 ✓	74.8 ✓	1.5	1.20 ✓	0.55 ✓	0.73 ✓
3382	74.8 ✓	76.3 ✓	1.5	8.23 ✓	0.78 ✓	0.23 ✓
3383	76.3 ✓	77.8 ✓	1.5	5.14 ✓	0.33 ✓	0.63 ✓
3384	77.8 ✓	79.3 ✓	1.5	6.17 ✓	0.28 ✓	0.73 ✓
3385	79.3 ✓	80.8 ✓	1.5	5.14 ✓	0.13 ✓	0.25 ✓
3386	80.8 ✓	82.3 ✓	1.5	6.17 ✓	0.28 ✓	0.70 ✓
3387	82.3 ✓	83.8 ✓	1.5	2.06 ✓	0.13 ✓	0.20 ✓
3388	83.8 ✓	85.3 ✓	1.5	2.06 ✓	0.10 ✓	0.30 ✓
3389	85.3 ✓	86.8 ✓	1.5	TR	TR	TR
3390	86.8 ✓	88.3 ✓	1.5	7.20 ✓	0.38 ✓	0.25 ✓
3391	88.3 ✓	89.8 ✓	1.5	3.09 ✓	0.05 ✓	0.03 ✓
3392	89.8 ✓	91.3 ✓	1.5	TR	TR	TR
3393	91.3 ✓	92.8 ✓	1.5	TR	TR	TR
	92.8 ✓	105.8 ✓	13.0	NOT ASSAYED		
3394	105.8 ✓	107.5 ✓	1.7	0.00 TR ✓	0.02 ✓	0.10 ✓
	107.5 ✓	122.8 ✓	15.3	0.00	0.00	0.00

LATITUDE LN  
DEPARTURE 10 W  
ELEVATION

DIP AT COLLAR -90°  
BEARING  
DEPTH 122.8 m (403 ft)

59.8m - 64.3 = 4.5m (15ft)  
Ag. 54.06 g/t Pb 4.55%  
Zn 5.28%



12.7.76 - 17.7.76

ASSAY NUMBER	SECTION		CORE LENGTH (M)	ASSAYS		
	FROM (M)	TO (M)		Ag g/t	Pb %	Zn %
3811	0.00 62.1	62.1 63.6	62.1 1.5	0.00 67.54	0.00 5.56	0.00 4.36
3812	63.6	65.1	1.5	43.54	2.90	2.50
3813	65.1	66.6	1.5	85.12	7.23	5.15
3814	66.6	68.1	1.5	TR	0.15	0.15
3815	68.1	69.6	1.5	18.17	1.33	1.23
3816	69.6	71.1	1.5	64.46	4.60	8.74
3817	71.1	72.6	1.5	32.23	2.60	3.40
3818	72.6	74.1	1.5	53.49	4.00	3.36
3819	74.1	75.6	1.5	114.86	10.26	5.90
3820	75.6	77.1	1.5	116.92	11.27	7.56
3821	77.1	78.6	1.5	73.71	6.96	5.36
3822	78.6	80.1	1.5	35.31	3.63	3.16
3823	80.1	81.6	1.5	42.51	3.65	3.80
3824	81.6	83.1	1.5	50.40	4.05	4.80
3825	83.1	84.6	1.5	49.37	4.10	4.30
3826	84.6	86.1	1.5	80.57	5.61	7.91
3827	86.1	87.6	1.5	58.63	3.55	8.75
3828	87.6	89.1	1.5	40.46	2.98	4.00
3829	89.1	91.6	1.5	18.03	0.80	1.28
3830	91.6	93.6	2.0	9.94	0.50	0.53
	93.6	102.7	9.1	0.00	0.00	0.00

LATITUDE 6N  
DEPARTURE 10W  
ELEVATION

DIP AT CORNER  
BEARING  
DEPTH 102.7m (337 ft)

62.1 - 66.6 = 4.5m (14.76 ft)  
Ag. 65.6 g/t. Pb 5.23%.  
Zn 4.00%.

62.1 - 89.1 = 27.0m (88.6 ft)

69.6 - 89.1 = 19.5m (64 ft)  
Ag 62.53 g/t.  
Pb 5.17%.  
Zn 5.46%.

Ag 57.10 g/t.  
Pb 4.69%.  
Zn 4.69%.

14.6.76 - 15.6.76

ASSAY NUMBER	SECTION		CORE LENGTH (M)	ASSAYS		
	FROM (M)	TO (M)		Ag g/t	Pb %	Zn %
3298	0.0 ✓	1.5 ✓	1.5	67.54 ✓	4.22 ✓	10.25 ✓
3299	1.5 ✓	3.0 ✓	1.5	66.51 ✓	4.14 ✓	8.21 ✓
3300	3.0 ✓	4.6 ✓	1.6	86.74 ✓	5.76 ✓	8.87 ✓
3401	4.6 ✓	5.2 ✓	0.6	8.23 ✓	0.68 ✓	1.45 ✓
3402	5.2 ✓	6.1 ✓	0.9	58.63 ✓	4.15 ✓	6.76 ✓
3403	6.1 ✓	7.6 ✓	1.5	78.86 ✓	5.55 ✓	5.86 ✓
3404	7.6 ✓	9.1 ✓	1.5	55.54 ✓	3.08 ✓	5.15 ✓
3405	9.1 ✓	10.7 ✓	1.6	10.97 ✓	0.55 ✓	0.45 ✓
3406	10.7 ✓	13.7 ✓	3.0	3.09 ✓	0.18 ✓	0.28 ✓
3407	13.7 ✓	16.5 ✓	2.8	3.09 ✓	0.18 ✓	0.30 ✓
3408	16.5 ✓	18.3 ✓	1.8	71.66 ✓	4.80 ✓	8.26 ✓
3409	18.3 ✓	19.8 ✓	1.5	50.40 ✓	3.13 ✓	6.73 ✓
3410	19.8 ✓	21.3 ✓	1.5	44.23 ✓	2.73 ✓	3.45 ✓
3411	21.3 ✓	22.9 ✓	1.6	32.23 ✓	1.93 ✓	3.33 ✓
3412	22.9 ✓	24.4 ✓	1.5	35.31 ✓	2.33 ✓	3.85 ✓
3413	24.4 ✓	25.9 ✓	1.5	28.46 ✓	1.48 ✓	3.10 ✓
3414	25.9 ✓	27.4 ✓	1.5	40.46 ✓	2.20 ✓	4.35 ✓
3415	27.4 ✓	29.0 ✓	1.6	28.46 ✓	1.53 ✓	2.18 ✓
3416	29.0 ✓	30.5 ✓	1.5	17.14 ✓	0.98 ✓	1.88 ✓
3417	30.5 ✓	32.0 ✓	1.5	35.31 ✓	1.80 ✓	3.75 ✓
3418	32.0 ✓	33.5 ✓	1.5	48.34 ✓	2.98 ✓	5.00 ✓
3419	33.5 ✓	35.1 ✓	1.6	52.46 ✓	3.25 ✓	3.90 ✓
3420	35.1 ✓	36.6 ✓	1.5	57.60 ✓	4.00 ✓	6.74 ✓
3421	36.6 ✓	38.4 ✓	1.8	51.43 ✓	3.20 ✓	4.25 ✓
3422	38.4 ✓	41.0 ✓	2.6	19.20 ✓	1.30 ✓	2.95 ✓
3423	41.0 ✓	42.7 ✓	1.7	31.20 ✓	2.00 ✓	3.96 ✓
3424	42.7 ✓	44.2 ✓	1.5	27.43 ✓	1.75 ✓	4.20 ✓
3425	44.2 ✓	45.7 ✓	1.5	25.37 ✓	1.93 ✓	2.58 ✓

LATITUDE 10891.951  
DEPARTURE 7625.063  
ELEVATION 1134.224

DIP AT COLLAR.  
BEARING.  
DEPTH 45.7 m.

0.0 - 9.1 m = 9.1 m (30 ft)

Ag 65.84 g/t.  
Pb 4.27 %  
Zn 7.18 %

16.5 - 21.3 m = 4.8 m (15.75 ft)

Ag 56.4 g/t.  
Pb 3.63 %  
Zn 6.28 %

25.9 - 27.4 = 1.5 m (5 ft) Ag 40.46 g/t, Pb 2.20%, Zn 4.35%

32.0 - 38.4 = 6.4 m (21 ft)

Ag 51.00 g/t.  
Pb 3.35 %  
Zn 4.92 %

18. 7. 76 - 19. 7. 76

ASSAY NUMBER	SECTION		CORE LENGTH (M)	ASSAYS		
	FROM (M)	TO (M)		Ag g/t	Pb %	Zn %
3856	0.0 ✓ 27.0 ✓	27.0 ✓ 28.5 ✓	27.0 ✓ 1.5 ✓	0.60 ✓ 55.54 ✓	0.00 ✓ 3.85 ✓	0.00 ✓ 6.22 ✓
3857	28.5 ✓ 31.3 ✓	31.3 ✓ 74.0 ✓	2.8 ✓ 42.7 ✓	24.34 ✓ 0.00 ✓	1.65 ✓ 0.00 ✓	2.65 ✓ 0.00 ✓

LATITUDE 6N

DIP AT COLLAR.

DEPARTURE 10W

BEARING.

ELEVATION

LENGTH. 74 m (243 ft)

27.0 - 28.5 = 1.5 m (5 ft) Ag 55.54 g/t, Pb 3.85%, Zn 6.22%

27.0 - 31.3 = 4.3 m (14 ft)

Ag 55.22 g/t.

Pb 2.42%

Zn 3.90%

now



15.6.76 . 16.6.76

ASSAY NUMBER	SECTION		CORE LENGTH (M)	ASSAYS		
	FROM (M)	TO (M)		Ag %	Pb %	Zn %
3426	0.0	1.5	1.5	91.89	5.46	10.31
3427	1.5	3.2	1.7	47.81	2.28	4.36
3428	3.2	4.1	0.9	6.17	0.18	0.33
3429	4.1	5.4	1.3	18.17	0.45	0.75
3430	5.4	7.1	1.7	1.03	0.02	0.05
3431	7.1	9.2	2.1	TR	0.01	0.08
3432	9.2	11.1	1.9	70.63	4.34	6.13
	11.1	19.1	8.0	NOT ASSAYED		
3433	19.1	21.3	2.2	41.49	2.53	3.66
3434	21.3	22.9	1.6	28.46	1.60	2.48
3435	22.9	24.4	1.5	67.54	4.43	6.90
3436	24.4	26.0	1.6	70.63	4.85	4.90
	26.0	43.4	17.4	NOT ASSAYED		
3437	43.4	45.0	1.6	3.09	0.13	0.23
3438	45.0	47.2	2.2	63.43	4.50	7.69
3439	47.2	48.8	1.6	55.54	3.78	7.21
3440	48.8	50.3	1.5	51.43	3.10	6.51
3441	50.3	51.8	1.5	15.09	0.73	1.38
3442	51.8	53.3	1.5	27.43	2.00	4.25
3443	53.3	54.9	1.6	27.43	1.75	2.33
3444	54.9	56.4	1.5	14.06	1.25	1.83
3445	56.4	57.9	1.5	25.37	2.68	1.80
3446	57.9	59.4	1.5	29.14	2.18	4.20
3447	59.4	61.0	1.6	29.14	1.98	3.25
3448	61.0	62.5	1.5	52.46	3.55	4.75
3449	62.5	64.0	1.5	75.77	5.29	9.89
	64.0	68.6	4.6	0.00	0.00	0.00

LATITUDE TN 10891.825  
 DEPARTURE TW 7625.101  
 ELEVATION 1136.46  
 DIP AT COLLAR +44° 52'  
 BEARING 225° 03' 33"  
 DEPTH 68.6 m (225 ft)

0.0 - 3.2 m = 3.2 m (10.5 ft)  
 Ag 68.21 g/t; Pb 3.77%; Zn 7.15%

9.2 - 11.1 = 1.9 m <sup>(6.0 ft)</sup>  
 Ag 70.63 g/t; Pb 4.34%; Zn 6.13%

19.1 - 26.0 = 6.9 m (22.6 ft)  
 Ag 50.89 g/t.  
 Pb 3.27%  
 Zn 4.38%

22.9 - 26.0 = 3.1 m (10 ft)  
 Ag 69.13 g/t  
 Pb 4.65% Zn 5.87%

45.0 - 53.3 = 8.3 m (27 ft)  
 Ag 44.5 g/t  
 Pb 2.97%  
 Zn 5.54%

57.9 - 64.0 = 6.1 m (20 ft)  
 Ag 46.34 g/t.  
 Pb 3.23%  
 Zn 5.49%

17.6.76 - 19.6.76

ASSAY NUMBER	SECTION		CORE LENGTH (M)	n		
	FROM (M)	TO (M)		Ag g/t	Pb %	Zn %
3450	0.0 ✓	1.5 ✓	1.5	9.94 ✓	0.45 ✓	1.28 ✓
3451	1.5 ✓	3.0 ✓	1.5	77.83 ✓	5.69 ✓	10.20 ✓
3452	3.0 ✓	4.6 ✓	1.6	38.40 ✓	2.08 ✓	6.74 ✓
3453	4.6 ✓	6.1 ✓	1.5	45.26 ✓	2.78 ✓	6.25 ✓
3454	6.1 ✓	7.6 ✓	1.5	90.86 ✓	5.00 ✓	10.71 ✓
3455	7.6 ✓	9.1 ✓	1.5	168.34 ✓	8.40 ✓	16.54 ✓
3456	9.1 ✓	10.7 ✓	1.6	208.80 ✓	9.30 ✓	18.49 ✓
	10.7 ✓	13.7 ✓	3.0	NOT ASSAYED		
3457	13.7 ✓	15.2 ✓	1.5	66.51 ✓	4.05 ✓	9.66 ✓
3458	15.2 ✓	16.8 ✓	1.6	59.31 ✓	3.75 ✓	6.15 ✓
	16.8 ✓	21.3 ✓	4.5	NOT ASSAYED		
3459	21.3 ✓	22.9 ✓	1.6	27.43 ✓	1.45 ✓	2.66 ✓
3460	22.9 ✓	24.4 ✓	1.5	24.34 ✓	1.08 ✓	4.10 ✓
3461	24.4 ✓	25.9 ✓	1.5	94.63 ✓	6.36 ✓	9.65 ✓
3462	25.9 ✓	27.4 ✓	1.5	100.80 ✓	6.40 ✓	12.35 ✓
3463	27.4 ✓	29.0 ✓	1.6	55.54 ✓	4.15 ✓	4.00 ✓
3464	29.0 ✓	31.0 ✓	2.0	3.09 ✓	0.15 ✓	0.50 ✓
	31.0 ✓	39.6 ✓	8.6	NOT ASSAYED		
3465	39.6 ✓	41.1 ✓	1.5	68.57 ✓	6.10 ✓	10.37 ✓
3466	41.1 ✓	42.7 ✓	1.6	46.29 ✓	3.45 ✓	7.86 ✓
3467	42.7 ✓	44.2 ✓	1.5	24.34 ✓	1.33 ✓	2.20 ✓
3468	44.2 ✓	45.7 ✓	1.5	23.31 ✓	1.33 ✓	3.40 ✓
3469	45.7 ✓	47.2 ✓	1.5	25.37 ✓	1.40 ✓	3.86 ✓
3470	47.2 ✓	48.8 ✓	1.6	27.43 ✓	2.13 ✓	2.86 ✓
3471	48.8 ✓	50.3 ✓	1.5	50.40 ✓	4.28 ✓	3.86 ✓
3472	50.3 ✓	51.8 ✓	1.5	17.14 ✓	1.48 ✓	2.70 ✓
3473	51.8 ✓	53.3 ✓	1.5	26.40 ✓	1.98 ✓	2.00 ✓
3474	53.3 ✓	54.9 ✓	1.6	16.11 ✓	1.13 ✓	1.36 ✓
3475	54.9 ✓	56.5 ✓	1.6	61.37 ✓	4.08 ✓	7.69 ✓
	56.5 ✓	76.2 ✓	19.7	0.00	0.00	0.00

LATITUDE TN 10892.665  
 DEPARTURE 16W. 1626.485  
 ELEVATION 1138.16

DIP AT COLLAR  $74^{\circ} 34'$   
 BEARING  $248^{\circ} 24' 17''$   
 DEPTH 16.2 m (250 ft)

1.5 - 10.7 = 9.2 m (30 ft)

Ag 105.32 g/t.

Pb 5.54%

Zn 11.51%

1.5 - 16.8 = 15.3 m (50 ft)

Ag 76.0 g/t.

Pb 4.12%

Zn 8.51%

13.7 - 16.8 = 3.1 m (<sup>10.0 ft</sup>) Ag 62.79 g/t

Pb 3.9% Zn 7.85%

1.5 - 29.0 = 27.5 m (90 ft)

Ag 59.13 g/t.

Pb 3.37%

Zn 6.55%

24.4 - 29.0 = 4.6 m (15 ft)

Ag 83.05 g/t Pb 5.60%

Zn 8.56%

39.6 - 42.7 = 3.1 m (10 ft) Ag 57.07 g/t

Pb 4.73% Zn 9.07%

48.8 - 50.3 = 1.5 m (5 ft) Ag 50.4 g/t. Pb 4.28%. Zn 3.86%.

54.9 - 56.5 = 1.6 m (5 1/4 ft) Ag 61.37 g/t. Pb 4.08%. Zn 7.69%.

NOTE

DDH # 117

PAGES 52 & 53

E.C.L.

10.7.76 - 10.7.76

ASSAY NUMBER	SECTION		CORE LENGTH (M)	ASSAYS		
	FROM (M)	TO (M)		Ag g/t	Pb %	Zn %
3831	0.0 ✓	3.0 ✓	3.0	44.23 ✓	2.38 ✓	5.00 ✓
3832	3.0 ✓	4.6 ✓	1.6	33.26 ✓	1.40 ✓	4.20 ✓
3833	4.6 ✓	6.1 ✓	1.5	26.40 ✓	1.10 ✓	2.80 ✓
3834	6.1 ✓	7.6 ✓	1.5	28.46 ✓	1.70 ✓	3.63 ✓
3835	7.6 ✓	9.6 ✓	2.0	53.49 ✓	3.00 ✓	6.05 ✓
	9.6 ✓	15.5 ✓	5.9	NO.1 ASSAYED		
3836	15.5 ✓	17.0 ✓	1.5	23.31 ✓	1.00 ✓	1.30 ✓
3837	17.0 ✓	18.5 ✓	1.5	10.63 ✓	4.20 ✓	7.96 ✓
3838	<del>18.5</del> 18.5 ✓	20.0 ✓	1.5	36.34 ✓	2.70 ✓	2.70 ✓
3839	20.0 ✓	21.5 ✓	1.5	50.40 ✓	3.00 ✓	5.93 ✓
3840	21.5 ✓	23.4 ✓	1.9	40.46 ✓	2.55 ✓	4.56 ✓
	23.4 ✓	61.0 ✓	37.6	0.00	0.00	0.00

LATITUDE TN

DIP AT COLLAR

DEPARTURE THW.

BEARING

ELEVATION

DEPTH. 61.0 m (200 ft).

0.0 - 3.0 = 3.0 m (10 ft) Ag 44.23 g/t, Pb 2.38%, Zn 5.00%.

0.0 - 9.6 = 9.6 m (31.5 ft)

Ag 39.08 g/t.

Pb 2.04%

Zn 4.53%

7.6 - 9.6 = 2.0 m (6.6 ft) Ag 53.49 g/t, Pb 3.00%, Zn 6.05%.

17.0 - 23.4 = 6.4 m (21 ft)

Ag 48.9 g/t.

Pb 3.08%

Zn 5.24%

18.7.76 - 19.7.76

ASSAY NUMBER	SECTION		CORE LENGTH	ASSAYS		
	FROM (M)	TO (M)		Ag g/t	Pb %	Zn %
3841	0.0 ✓	4.6 ✓	4.6	130.97	6.56 ✓	13.19 ✓
3842	4.6 ✓	6.1 ✓	1.5	87.77 ✓	4.98 ✓	8.60 ✓
3843	6.1 ✓	7.6 ✓	1.5	80.57 ✓	4.98 ✓	9.46 ✓
3844	7.6 ✓	8.6 ✓	1.0	106.97 ✓	6.30 ✓	9.89 ✓
	8.6 ✓	57.9 ✓	49.3	NOT ASSAYED		
3845	57.9 ✓	59.4 ✓	1.5	50.40 ✓	3.08 ✓	4.70 ✓
3846	59.4 ✓	61.0 ✓	1.6	26.40 ✓	1.63 ✓	2.43 ✓
3847	61.0 ✓	62.5 ✓	1.5	111.09 ✓	7.53 ✓	11.05 ✓
3848	62.5 ✓	64.0 ✓	1.5	53.49 ✓	3.40 ✓	4.86 ✓
3849	64.0 ✓	65.5 ✓	1.5	8.23 ✓	0.13 ✓	1.05 ✓
3850	65.5 ✓	67.1 ✓	1.6	55.54 ✓	3.50 ✓	3.30 ✓
3851	67.1 ✓	68.6 ✓	1.5	27.43 ✓	1.28 ✓	0.65 ✓
3852	68.6 ✓	70.1 ✓	1.5	21.26 ✓	0.75 ✓	1.42 ✓
3853	70.1 ✓	71.6 ✓	1.5	8.91 ✓	0.10 ✓	0.40 ✓
3854	71.6 ✓	73.2 ✓	1.6	12.00 ✓	0.08 ✓	0.55 ✓
3855	73.2 ✓	76.2 ✓	3.0	30.17 ✓	1.98 ✓	2.60 ✓
	76.2 ✓	103.6 ✓	27.4	0.00	0.00	0.00

LATITUDE 2N  
 DEPARTURE 70W  
 ELEVATION

DIP AT COLLAR  
 BEARING  
 DEPTH 103.6m (340 ft)

0.0 - 8.6 = 8.6m (28.23 ft)

Ag 111.85 g/t  
 Pb 5.98 %  
 Zn 11.36 %

57.9 - 67.1 = 9.2m (30.2 ft)

Ag 50.64 g/t  
 Pb 3.20 %  
 Zn 4.53 %

E.C.L.

19.6.76 - 20.6.76

ASSAY NUMBER	SECTION		CORE LENGTH	ASSAYS		
	From (m)	To (m)		Ag g/t	Pb %	Zn %
	0.0	61.0	61.0	0.00	0.00	0.00
			NIL			

LATITUDE TN. 10895.715

DIP AT COLLAR 0°

DEPARTURE 16W

BEARING 40° 07' 18"

ELEVATION 1134.219

DEPTH 61 m (200 ft)



20.7.76 - 21.7.76

ASSAY NUMBER	SECTION		CORE LENGTH	ASSAYS		
	FROM (M)	TO (M)		Ag g/t	Pb %	Zn %
3858	0.0 ✓	2.7 ✓	2.7	58.63	3.15	5.10
	2.7 ✓	30.5 ✓	27.8	NOT ASSAYED		
3859	30.5 ✓	32.0 ✓	1.5	9.94	0.38	0.78
	32.0 ✓	37.8 ✓	5.8	NOT ASSAYED		
3860	37.8 ✓	40.7 ✓	2.9	8.23	0.28	0.50
	40.7	65.5	24.8			

LATITUDE 2N

DIP AT COLLAR -60°

DEPARTURE 10W

BEARING 224°

ELEVATION

DEPTH 65.5 m (215 ft)

0.0 - 2.7 = 2.7m (9.0ft)

Ag 58.63 g/t, Pb 3.15%, Zn 5.10%

Hole 121

NOT COMPLETE

40.7 - 65.5

00 . 00 . 00

E.C.I.

21.6.76 - 22.6.76

ASSAY NUMBER	SECTION		CORE LENGTH (m)	ASSAYS		
	FROM (m)	TO (m)		Ag g/t	Pb %	Zn %
	0.0	91.4	91.4	0.00	0.00	0.00
			N/A.			

LATITUDE TN  
 DEPARTURE 16W  
 ELEVATION

DIP AT COLLAR  
 BEARING  
 DEPTH 91.4 m (300 ft)

E.C.J.

21.7.76 - 24.7.76

ASSAY NUMBER	SECTION		CORE LENGTH	ASSAYS		
	FROM (M)	TO (M)		Ag g/t	Pb %	Zn %
3861	0.0 ✓	3.0 ✓	3.0	80.51 ✓	4.25 ✓	8.15 ✓
3862	3.0 ✓	4.6 ✓	1.6	89.83 ✓	5.26 ✓	10.09 ✓
3863	4.6 ✓	6.1 ✓	1.5	10.63 ✓	3.88 ✓	7.72 ✓
3864	6.1 ✓	7.6 ✓	1.5	91.89 ✓	4.98 ✓	8.27 ✓
3865	7.6 ✓	9.1 ✓	1.5	99.77 ✓	6.10 ✓	9.44 ✓
3866	9.1 ✓	10.7 ✓	1.6	54.51 ✓	2.20 ✓	4.80 ✓
3867	10.7 ✓	12.2 ✓	1.5	34.29 ✓	2.38 ✓	6.50 ✓
3868	12.2 ✓	13.7 ✓	1.5	54.51 ✓	2.85 ✓	6.33 ✓
3869	13.7 ✓	15.2 ✓	1.5	39.43 ✓	2.38 ✓	6.82 ✓
3870	15.2 ✓	16.8 ✓	1.6	69.60 ✓	3.08 ✓	6.17 ✓
3871	16.8 ✓	18.3 ✓	1.5	85.72 ✓	4.48 ✓	7.45 ✓
3872	18.3 ✓	21.3 ✓	3.0	43.54 ✓	2.11 ✓	2.13 ✓
3873	21.3 ✓	22.9 ✓	1.6	2.74 ✓	0.10 ✓	0.15 ✓
3874	22.9 ✓	24.4 ✓	1.5	92.92 ✓	4.50 ✓	5.15 ✓
3875	24.4 ✓	25.9 ✓	1.5	55.54 ✓	2.85 ✓	2.68 ✓
	25.9 ✓	31.0 ✓	4.1	NOT ASSAYED		
3876	31.0 ✓	32.5 ✓	1.5	75.77 ✓	4.65 ✓	8.35 ✓
3877	32.5 ✓	34.0 ✓	1.5	62.40 ✓	4.55 ✓	7.97 ✓
	34.0 ✓	45.7 ✓	11.7	NOT ASSAYED		
3878	45.7 ✓	47.2 ✓	1.5	174.52 ✓	10.75 ✓	19.60 ✓
3879	47.2 ✓	48.8 ✓	1.6	185.49 ✓	11.06 ✓	23.63 ✓
3880	48.8 ✓	50.3 ✓	1.5	60.34 ✓	4.98 ✓	8.82 ✓
3881	50.3 ✓	51.8 ✓	1.5	82.63 ✓	5.82 ✓	9.35 ✓
3882	51.8 ✓	53.3 ✓	1.5	60.34 ✓	4.45 ✓	7.98 ✓
3883	53.3 ✓	54.9 ✓	1.6	124.12 ✓	9.53 ✓	18.15 ✓
3884	54.9 ✓	56.4 ✓	1.5	15.09 ✓	0.09 ✓	0.30 ✓
3885	56.4 ✓	57.9 ✓	1.5	18.17 ✓	0.20 ✓	0.15 ✓
3886	57.9 ✓	59.4 ✓	1.5	9.94 ✓	0.08 ✓	0.45 ✓
3887	59.4 ✓	61.0 ✓	1.6	15.09 ✓	0.15 ✓	0.60 ✓
3888	61.0 ✓	62.5 ✓	1.5	15.09 ✓	0.35 ✓	0.78 ✓
3889	62.5 ✓	64.0 ✓	1.5	21.26 ✓	1.33 ✓	1.83 ✓
3890	64.0 ✓	65.5 ✓	1.5	78.86 ✓	6.82 ✓	9.68 ✓
3891	65.5 ✓	67.1 ✓	1.6	20.23 ✓	1.00 ✓	1.40 ✓
3892	67.1 ✓	68.6 ✓	1.5	19.20 ✓	0.45 ✓	0.70 ✓
3893	68.6 ✓	70.1 ✓	1.5	17.14 ✓	0.93 ✓	1.10 ✓
3894	70.1 ✓	71.6 ✓	1.5	5.14 ✓	0.10 ✓	0.33 ✓
3895	<del>71.6</del> 71.6 ✓	73.2 ✓	1.6	10.97 ✓	0.15 ✓	0.58 ✓
3896	73.2 ✓	74.7 ✓	1.5	7.20 ✓	0.08 ✓	0.30 ✓
3897	74.7 ✓	76.2 ✓	1.5	7.20 ✓	0.10 ✓	0.50 ✓
3898	76.2 ✓	77.7 ✓	1.5	6.17 ✓	0.12 ✓	0.35 ✓
3899	77.7 ✓	79.2 ✓	1.5	7.20 ✓	0.13 ✓	0.68 ✓
3900	79.2 ✓	80.8 ✓	1.6	27.43 ✓	1.30 ✓	2.53 ✓
3901	NOTE 80.8 ✓	82.0 ✓	1.2	65.49 ✓	3.65 ✓	6.14 ✓
	82.0 ✓	101.5 ✓	19.5	NOT ASSAYED		
3910	101.5 ✓	103.6 ✓	2.1	70.36 ✓	4.85 ✓	6.24 ✓
3911	103.6 ✓	105.2 ✓	1.6	30.17 ✓	2.00 ✓	1.36 ✓
3912	105.2 ✓	106.7 ✓	1.5	28.46 ✓	3.95 ✓	1.73 ✓
3913	106.7 ✓	108.2 ✓	1.5	77.83 ✓	7.37 ✓	3.75 ✓
3914	108.2 ✓	109.7 ✓	1.5	28.46 ✓	2.30 ✓	1.33 ✓
3915	109.7 ✓	111.3 ✓	1.6	9.94 ✓	0.40 ✓	0.30 ✓

80.8-82.0 = 1.2 (4 ft)

Ag 65.49 g/t Pb 3.65% Zn 6.14%

101.5-108.2 = 6.7m (22 ft)

Ag 53.14 g/t Pb 4.53% Zn 3.51%

3871	0.0	3.0	3.0	80.57	4.25	8.75
3872	3.0	4.0	1.0	89.83	5.26	10.09
3873	4.6	6.1	1.5	70.03	3.88	7.72
3874	3.0	4.0	1.0	89.83	5.26	10.09
3875	24.4	25.9	1.5	55.54	2.85	2.68
3876	31.0	31.0	4.1	NOT ASSAYED		
3877	32.5	34.0	1.5	62.40	4.55	7.97
3878	45.7	45.7	11.7	NOT ASSAYED		
3879	47.2	48.8	1.6	185.49	11.06	23.63
3880	48.8	50.3	1.5	60.34	4.98	8.82
3881	50.3	51.8	1.5	82.63	5.82	9.35
3882	51.8	53.3	1.5	60.34	4.45	7.98
3883	53.3	54.9	1.6	124.12	9.53	18.75
3884	54.9	56.4	1.5	15.09	0.09	0.30
3885	56.4	57.9	1.5	18.17	0.20	0.15
3886	57.9	59.4	1.5	9.94	0.08	0.45
3887	59.4	61.0	1.6	15.09	0.15	0.60
3888	61.0	62.5	1.5	15.09	0.35	0.78
3889	62.5	64.0	1.5	21.26	1.33	1.83
3890	64.0	65.5	1.5	78.86	6.82	9.68
3891	65.5	67.1	1.4	20.23	1.00	1.40
3892	67.1	68.6	1.5	19.20	0.45	0.70
3893	68.6	70.1	1.5	17.14	0.93	1.10
3894	70.1	71.6	1.5	5.14	0.10	0.33
3895	71.6	73.2	1.6	10.97	0.15	0.58
3896	73.2	74.7	1.5	7.20	0.08	0.30
3897	74.7	76.2	1.5	7.20	0.10	0.50
3898	76.2	77.7	1.5	6.17	0.12	0.35
3899	77.7	79.2	1.5	7.20	0.13	0.68
3900	79.2	80.8	1.6	27.43	1.30	2.53
3901	80.8	82.0	1.2	65.49	3.65	6.14
3910	101.5	103.6	2.1	70.36	4.85	6.24
3911	103.6	105.2	1.6	30.17	2.00	1.36
3912	105.2	106.7	1.5	28.46	3.95	1.73
3913	106.7	108.2	1.5	77.83	7.37	3.75
3914	108.2	109.7	1.5	28.46	2.30	1.33
3915	109.7	111.3	1.6	9.94	0.40	0.30
3916	111.3	112.8	1.5	8.91	0.15	0.12
3922	112.8	114.3	1.5	12.00	0.23	0.30
3923	114.3	115.8	1.5	13.03	0.22	0.10
3924	115.8	117.3	1.5	12.00	0.20	0.15
3925	117.3	118.9	1.6	31.20	2.40	2.80

NOTE

101.5-108.2-6.7m (22ft)  
Hg 53.14 g/L Pb 4.53 g/L Zn 3.51 g/L

80.8-82.0-1.2 (4ft)  
Hg 65.49 g/L Pb 3.65 g/L Zn 6.14 g/L

NOTE

82.0-101.5-19.5  
NOT ASSAYED

LATITUDE 2N  
DEPARTURE 70W  
ELEVATION

DIP AT COLLAR  
BEARING  
DEPTH 118.9 m (390 ft.)

0.0 - 18.3 = 18.3 m (60 ft)

Ag 70.95 g/t.

Pb 3.84%

Zn 7.58%

0 - 24.4 = 24.4 m (80.0 ft)

Ag 64.46 g/t.

Pb 3.42%

Zn 6.27%

0 - 34.0 = 34.0 m

(111.5 ft)

Ag 46.07 g/t.

Pb 2.99%

Zn 5.34%

22.9 - 24.4 = 1.5 m (5.0 ft)

Ag 92.92 g/t. Pb 4.50%

Zn 5.15%

31.0 - 34.0 = 3.0 m (10 ft) Ag 69.09 g/t.

Pb 4.6% Zn 8.16%

0.0 - 54.9 = 54.9 m (180 ft)

Ag 47.84 g/t.

Pb 3.16%

Zn 5.79%

45.7 - 54.9 = 9.2 m (30 ft)

Ag 115.45 g/t.

Pb 7.82%

Zn 14.83%

64.0 - 65.5 = 1.5 m (5.0 ft)

Ag 78.86 g/t Pb 6.82%

Zn 9.68%



22.0.76 - 23.6.76

ASSAY	SECTION	CORE	ASSAYS
-------	---------	------	--------

NUMBER	from (cm) / to (cm)	LENGTH (m)	Ag %	Pb %	Zn %
3476	0.0	1.5	27.43	2.00	2.15
3477	1.5	3.0	27.43	2.08	3.65
3478	3.0	4.6	40.46	2.63	4.60
3479	4.6	6.1	21.26	1.43	4.00
3480	6.1	7.6	25.37	1.75	4.30
3481	7.6	9.1	24.34	2.00	3.65
3482	9.1	10.7	26.40	2.00	3.75
3483	10.7	12.2	43.54	2.73	5.68
3484	12.2	13.7	52.46	3.13	7.39
3485	13.7	15.2	67.54	4.35	8.13
3486	15.2	16.8	45.77	5.90	6.36
3487	16.8	18.3	89.85	5.79	9.36
3488	18.3	19.5	77.83	5.36	7.21
3489	19.5	20.8	20.23	1.35	2.73
3490	20.8	25.9	22.23	1.58	2.74
3491	25.9	29.0	59.31	2.58	4.35
3492	29.0	30.5	17.14	0.73	1.25
3493	30.5	32.0	22.29	1.45	1.05
3494	32.0	33.5	33.26	1.48	2.95
3495	33.5	35.1	38.40	1.87	3.85
3496	35.1	36.6	43.54	1.78	2.88
3497	36.6	37.6	85.72	5.75	6.77
3498	37.6	38.7	12.1	NOT ASSAYED	NOT ASSAYED
3498	41.1	41.1	12.17	8.09	17.89
3499	41.1	42.7	22.97	14.98	22.56
3500	45.0	47.2	12.5.14	6.71	14.90
3501	47.2	48.8	80.57	6.27	5.15
3502	48.8	50.3	70.63	5.24	6.32
3503	50.3	51.8	45.26	3.15	3.85
	51.8	91.4	0.00	0.00	0.00

LATITUDE  
DEPARTURE  
ELEVATION

DIP AT COLLAR

BEARING

DEPTH 91.4 m (300 ft)

$30.4 - 4.6 = 1.6 \text{ m (5\frac{1}{4} \text{ ft})}$  Ag 40.46 g/t, Pb 2.63% Zn 4.60%

$0.0 - 10.7 = 10.7 \text{ m (35 ft)}$

NOW,

Ag 27.63 g/t

Pb 1.99%

Zn 3.74%

$10.7 - 19.5 = 8.8 \text{ m (29 ft)}$

Ag 67.58

Pb 4.53

Zn 1.35

$27.4 - 29.0 = 1.6 \text{ m (5\frac{1}{4} \text{ ft})}$  Ag 59.31 g/t, Pb 2.58% Zn 4.35%

$37.6 - 51.8 = 14.2 \text{ m (46\frac{1}{2} \text{ ft})}$

Ag 74.06 g/t

Pb 6.26%

Zn 10.00%

21.7.76 - 29.7.76

ASSAY NUMBER	SECTION		CORE LENGTH	ASSAYS		
	FROM (M)	TO (M)		Ag g/t	Pb %	Zn %
3759	0.0 ✓	1.5 ✓	1.5	147.09 ✓	13.26 ✓	30.48 ✓
3760	1.5 ✓	3.0 ✓	1.5	116.92 ✓	5.92 ✓	10.11 ✓
3761	3.0 ✓	4.4 ✓	1.4	85.72 ✓	4.10 ✓	9.96 ✓
3762	4.6 ✓	6.1 ✓	1.5	141.26 ✓	6.96 ✓	11.38 ✓
3763	6.1 ✓	8.1 ✓	2.0	103.89 ✓	6.01 ✓	8.95 ✓
3764	8.1 ✓	10.1 ✓	2.0	105.94 ✓	5.72 ✓	9.92 ✓
3765	10.1 ✓	12.1 ✓	2.0	58.63 ✓	4.15 ✓	9.96 ✓
3766	12.1 ✓	14.1 ✓	2.0	100.80 ✓	6.27 ✓	13.89 ✓
3767	14.1 ✓	16.1 ✓	2.0	126.17 ✓	7.71 ✓	19.90 ✓
3768	16.1 ✓	18.1 ✓	2.0	151.37 ✓	9.26 ✓	17.66 ✓
3769	18.1 ✓	20.1 ✓	2.0	149.14 ✓	8.71 ✓	24.30 ✓
3770	20.1 ✓	22.1 ✓	2.0	162.52 ✓	9.81 ✓	26.75 ✓
3771	22.1 ✓	24.1 ✓	2.0	142.29 ✓	7.71 ✓	14.10 ✓
3772	24.1 ✓	26.1 ✓	2.0	77.83 ✓	5.70 ✓	14.15 ✓
3773	26.1 ✓	28.1 ✓	2.0	92.92 ✓	5.92 ✓	12.78 ✓
3774	28.1 ✓	30.1 ✓	2.0	99.77 ✓	6.25 ✓	12.57 ✓
3775	30.1 ✓	32.1 ✓	2.0	146.06 ✓	8.66 ✓	14.50 ✓
3776	32.1 ✓	34.1 ✓	2.0	184.46 ✓	10.75 ✓	19.40 ✓
3777	34.1 ✓	36.1 ✓	2.0	81.60 ✓	5.20 ✓	11.07 ✓
3778	36.1 ✓	38.1 ✓	2.0	59.31 ✓	4.88 ✓	8.15 ✓
3779	38.1 ✓	40.1 ✓	2.0	93.94 ✓	6.76 ✓	9.20 ✓
3780	40.1 ✓	42.1 ✓	2.0	75.77 ✓	4.95 ✓	10.11 ✓
3781	42.1 ✓	45.1 ✓	3.0	5.14 ✓	0.48 ✓	0.70 ✓
	45.1 ✓	52.1 ✓	7.0	NOT ASSAYED		
3782	52.1 ✓	53.6 ✓	1.5	87.77 ✓	6.37 ✓	8.46 ✓
3783	53.6 ✓	55.6 ✓	2.0	120.00 ✓	7.35 ✓	13.99 ✓
3784	55.6 ✓	57.3 ✓	1.7	78.86 ✓	4.70 ✓	7.80 ✓
3785	57.3 ✓	58.8 ✓	1.5	114.86 ✓	7.36 ✓	11.80 ✓
3786	58.8 ✓	60.3 ✓	1.5	67.54 ✓	4.05 ✓	6.54 ✓
3787	60.3 ✓	61.8 ✓	1.5	110.06 ✓	6.80 ✓	12.63 ✓
3788	61.8 ✓	63.3 ✓	1.5	35.31 ✓	2.15 ✓	2.90 ✓
3789	63.3 ✓	64.8 ✓	1.5	30.17 ✓	1.85 ✓	2.78 ✓
3790	64.8 ✓	66.3 ✓	1.5	22.29 ✓	0.83 ✓	1.38 ✓
3791	66.3 ✓	67.8 ✓	1.5	14.06 ✓	0.23 ✓	0.83 ✓
3792	67.8 ✓	69.3 ✓	1.5	20.23 ✓	0.65 ✓	0.78 ✓
3793	69.3 ✓	71.3 ✓	2.0	9.94 ✓	0.60 ✓	1.05 ✓
3794	71.3 ✓	72.8 ✓	1.5	10.97 ✓	0.20 ✓	0.25 ✓
3795	72.8 ✓	74.3 ✓	1.5	100.8 ✓	6.43 ✓	11.36 ✓
3796	74.3 ✓	75.8 ✓	1.5	91.89 ✓	6.57 ✓	10.85 ✓
3797	75.8 ✓	77.3 ✓	1.5	35.31 ✓	3.50 ✓	6.06 ✓
3798	77.3 ✓	78.8 ✓	1.5	50.40 ✓	3.38 ✓	8.38 ✓
3799	78.8 ✓	80.3 ✓	1.5	82.63 ✓	5.63 ✓	16.35 ✓
3800	80.3 ✓	81.8 ✓	1.5	96.69 ✓	7.07 ✓	19.28 ✓
4001	81.8 ✓	83.3 ✓	1.5	209.83 ✓	14.46 ✓	25.37 ✓
4002	83.3 ✓	84.8 ✓	1.5	54.51 ✓	4.00 ✓	9.86 ✓
4003	84.8 ✓	86.3 ✓	1.5	78.51 ✓	4.75 ✓	13.50 ✓
4004	86.3 ✓	87.8 ✓	1.5	151.20 ✓	9.71 ✓	21.69 ✓
4005	87.8 ✓	89.3 ✓	1.5	76.80 ✓	4.10 ✓	10.77 ✓
4063	89.3 ✓	90.8 ✓	1.5	114.86 ✓	8.66 ✓	18.01 ✓
4064	90.8 ✓	92.3 ✓	1.5	43.54 ✓	2.98 ✓	1.24 ✓

LATITUDE LN

DIP AT CORNER. °

DEPARTURE 10W.

BEARING 044°

ELEVATION

DEPTH

92.8 m (303 ft).

0.0 - 42.1 = 42.1 m (138 ft)

Ag 113.58 g/t.

Pb 7.00%.

Zn 14.46%.

0 - 61.8 = 61.8 m (203 ft)

Ag 90.78 g/t.

Pb 5.73%.

Zn 11.47%.

52.1 - 61.8 = 9.7 m (32 ft)

Ag 97.36 g/t.

Pb 6.14%.

Zn 10.35%.

0.0 = 90.8 m = 90.8 m (298 ft).

Ag 84.54 g/t.

Pb 5.33%.

Zn 10.81%.

72.8 - 90.8 = 18.0 m (59 ft) Ag 95.27 g/t.

Pb 6.12%.

Zn 14.29%.

24.6.76 - 2.7.76

ASSAY NUMBER	SECTION		CORE LENGTH	ASSAYS		
	FROM (M)	TO (M)		Ag g/t	Pb%	Zn%
3504	0.0 ✓	4.6 ✓	4.6	19.20 ✓	1.53 ✓	3.13 ✓
3505	4.6 ✓	6.1 ✓	1.5	32.23 ✓	2.00 ✓	6.08 ✓
3506	6.1 ✓	7.6 ✓	1.5	37.37 ✓	2.40 ✓	3.65 ✓
3507	7.6 ✓	9.1 ✓	1.5	28.46 ✓	1.93 ✓	2.53 ✓
3508	9.1 ✓	10.7 ✓	1.5	31.20 ✓	1.63 ✓	3.38 ✓
3509	10.7 ✓	12.2 ✓	1.5	37.37 ✓	2.05 ✓	4.65 ✓
3510	12.2 ✓	13.7 ✓	1.5	34.29 ✓	2.70 ✓	4.30 ✓
3511	13.7 ✓	15.2 ✓	1.5	45.26 ✓	2.90 ✓	6.32 ✓
3512	15.2 ✓	16.8 ✓	1.6	40.46 ✓	2.80 ✓	4.68 ✓
3513	16.8 ✓	18.3 ✓	1.5	37.37 ✓	2.45 ✓	4.20 ✓
3514	18.3 ✓	19.8 ✓	1.5	39.43 ✓	2.49 ✓	5.15 ✓
3515	19.8 ✓	21.3 ✓	1.5	74.74 ✓	5.94 ✓	6.05 ✓
3516	21.3 ✓	22.9 ✓	1.6	77.83 ✓	6.71 ✓	3.95 ✓
3517	22.9 ✓	24.4 ✓	1.5	50.40 ✓	4.50 ✓	2.90 ✓
3518	24.4 ✓	25.9 ✓	1.5	55.54 ✓	4.39 ✓	3.45 ✓
3519	25.9 ✓	27.4 ✓	1.5	95.66 ✓	7.56 ✓	3.80 ✓
3520	27.4 ✓	29.0 ✓	1.6	87.77 ✓	5.99 ✓	9.37 ✓
3521	29.0 ✓	30.5 ✓	1.5	65.49 ✓	4.45 ✓	8.34 ✓
3522	30.5 ✓	32.0 ✓	1.5	70.63 ✓	4.65 ✓	9.61 ✓
3523	32.0 ✓	33.5 ✓	1.5	84.69 ✓	4.10 ✓	8.23 ✓
3524	33.5 ✓	35.1 ✓	1.6	83.66 ✓	4.85 ✓	9.08 ✓
3525	35.1 ✓	36.6 ✓	1.5	74.74 ✓	4.70 ✓	7.98 ✓
3526	36.6 ✓	38.1 ✓	1.5	77.83 ✓	4.70 ✓	8.38 ✓
3527	38.1 ✓	39.6 ✓	1.5	65.49 ✓	4.48 ✓	6.70 ✓
3528	39.6 ✓	41.1 ✓	1.5	65.49 ✓	4.21 ✓	7.62 ✓
3529	41.1 ✓	42.7 ✓	1.6	114.17 ✓	7.36 ✓	13.69 ✓
3530	42.7 ✓	44.2 ✓	1.5	65.49 ✓	4.51 ✓	7.41 ✓
3531	44.2 ✓	45.7 ✓	1.5	78.86 ✓	5.42 ✓	7.93 ✓
3532	45.7 ✓	47.2 ✓	1.5	67.54 ✓	3.73 ✓	4.80 ✓
3533	<del>47.2</del> 47.2 ✓	48.8 ✓	1.6	82.63 ✓	5.71 ✓	10.07 ✓
3534	48.8 ✓	50.3 ✓	1.5	100.80 ✓	7.34 ✓	10.12 ✓
3535	50.3 ✓	51.8 ✓	1.6	46.29 ✓	3.48 ✓	3.30 ✓
3536	51.8 ✓	54.9 ✓	3.1	8.91 ✓	0.61 ✓	1.30 ✓
3537	54.9 ✓	58.3 ✓	3.4	17.14 ✓	1.12 ✓	2.33 ✓
	58.3 ✓	74.0 ✓	16.7	NOT ASSAYED		

DDH U 126 continued on

Pages 70 & 71

LATITUDE  $76 \times 200$ 

DIP AT COLLAR

DEPARTURE  $760$ 

BEARING

ELEVATION

LENGTH  $144.8 \text{ m (475 ft)}$  $4.6 - 7.6 = 3.0 \text{ m (10 ft)}$  Ag.  $34.8 \text{ g/t}$ Pb.  $2.20\%$  Zn  $4.87\%$  $0.0 - 51.8 = 51.8 \text{ m (170 ft)}$ Ag  $51.12 \text{ g/t}$ Pb  $4.03\%$ Zn  $6.11\%$  $10.7 - 51.8 = 41.1 \text{ m (135 ft)}$ Ag  $67.72 \text{ g/t}$ Pb  $4.33\%$ Zn  $6.77\%$

ASSAY NUMBER	SECTION		CORE LENGTH	ASSAYS		
	FROM (m)	TO (m)		Ag g/t	Pb %	Zn %
3538	74.0	76.2	2.2	8.91	0.48	0.98
3539	76.2	77.7	1.5	22.29	1.20	2.20
3540	77.7	79.2	1.5	93.94	5.53	9.58
3541	79.2	80.8	1.6	70.63	4.63	7.31
3542	80.8	82.3	1.5	40.46	2.10	3.40
3543	82.3	83.8	1.5	45.26	3.53	4.70
3544	83.8	85.3	1.5	42.51	2.93	4.95
3545	85.3	86.9	1.6	12.00	0.44	0.48
3546	86.9	88.4	1.5	21.26	1.42	2.43
3547	88.4	89.9	1.5	51.43	3.10	4.70
3548	89.9	91.4	1.5	88.80	6.88	9.96
3549	91.4	93.0	1.6	42.51	3.15	4.05
3550	93.0	94.5	1.5	21.26	1.67	1.08
3551	94.5	96.0	1.5	47.31	4.10	4.90
3552	96.0	97.5	1.5	98.74	4.73	8.45
3553	97.5	99.1	1.6	50.40	3.18	5.50
3554	99.1	100.6	1.5	48.84	3.28	7.06
3555	100.6	102.1	1.5	113.14	6.70	9.36
3556	102.1	103.6	1.5	82.63	6.35	6.07
3557	103.6	105.2	1.6	58.63	3.38	3.10
3558	105.2	107.5	2.3	51.43	3.63	2.95
	107.5	111.0	3.5	NOT ASSAYED		
3559	111.0	112.8	1.8	20.23	1.00	1.33
	112.8	118.5	5.7	NOT ASSAYED		
3560	118.5	120.4	1.9	29.14	2.00	2.80
3561	120.4	121.9	1.5	69.60	4.38	5.05
3562	121.9	123.4	1.5	44.23	3.10	4.65
3563	123.4	125.0	1.6	72.69	4.55	7.51
3564	125.0	126.5	1.5	87.77	5.88	8.98
3565	126.5	128.0	1.5	44.23	2.18	3.30
3566	128.0	129.5	1.5	52.46	3.88	5.50
3567	129.5	131.1	1.6	42.51	2.83	5.30
3568	131.1	132.6	1.5	26.40	1.73	3.00
3569	132.6	134.1	1.5	8.91	0.08	0.50
3570	134.1	135.6	1.5	9.94	0.13	0.40
3571	135.6	137.2	1.6	29.43	1.55	1.88
	137.2	144.8	7.6	0.00	0.00	0.00

LATITUDE  
DEPARTURE  
ELEVATION

DIP AT COLLAR  
BEARING.  
DEPTH.

$$77.7 - 85.3 = 7.6 \text{ m (25 ft)}$$

Ag 58.72 g/t.

Pb 3.96%

Zn 6.01%

$$77.7 - 107.5 = 29.8 \text{ m (98 ft)}$$

Ag 56.56 g/t.

Pb 3.73%

Zn 4.97%

$$88.4 - 107.5 = 19.1 \text{ m (63 ft)}$$

Ag 62.21 g/t

Pb 4.10%

Zn 5.13%

$$120.4 - 131.1 = 10.7 \text{ m (35 ft)}$$

Ag 59.04 g/t

Pb 3.83%

Zn 5.77%

ASSAY NUMBER

ASSAY

SECTION

COKE

FROM (m) / TO (m) LENGTH Ag % Pb % Zn %

ASSAY

ELEVATION

DEPARTURE

HATITUDE

DIP AT CORNER

BEARING

DEPTH. ± 5.7 m (150 ft)

ASSAY NUMBER	SECTION	COKE	FROM (m) / TO (m) LENGTH	Ag %	Pb %	Zn %
4006			0.0 / 3.0	140.23	9.41	13.98
4007			3.0 / 4.6	137.14	10.72	18.36
4008			4.6 / 5.8	17.14	1.28	2.48
4009			5.8 / 7.3	5.14	0.25	0.42
4010			7.3 / 8.7	93.94	7.30	10.76
4011			8.7 / 10.2	96.69	6.20	15.01
4012			10.2 / 11.7	30.17	1.53	2.50
4013			11.7 / 13.7	87.77	8.26	12.41
4014			13.7 / 15.2	95.66	4.60	10.51
4015			15.2 / 16.8	80.57	6.90	12.04
4016			16.8 / 18.3	65.49	5.80	11.07
4017			18.3 / 19.8	36.34	2.65	5.15
4018			19.8 / 21.3	63.09	6.28	12.48
4019			21.3 / 22.9	99.77	5.85	10.77
4020			22.9 / 24.4	96.69	6.18	12.90
4021			24.4 / 25.9	100.60	7.27	15.27
4022			25.9 / 27.4	20.23	0.55	1.63
4023			27.4 / 29.0	8.23	0.15	0.73
4024			29.0 / 30.5	60.34	4.72	6.85
4025			30.5 / 32.0	24.40	1.88	2.15
4026			32.0 / 33.5	8.91	0.38	0.68
4027			33.5 / 35.1	4.11	0.15	0.50
4028			35.1 / 36.6	5.14	0.28	0.55
4029			36.6 / 38.2	8.23	0.53	0.82
4030			38.2 / 45.7	0.00	0.00	0.00

0.0 - 30.5 = 30.5m (100ft)

Ag 14.72 g/t

Pb 5.37%

Zn 9.61%



2.7.76 -

ASSAY NUMBER	SECTION		CORE LENGTH	ASSAYS		
	FROM (m)	TO (m)		Ag g/t	Pb %	Zn %
3572	0.0 ✓	4.6 ✓	4.6	47.31 ✓	3.10 ✓	4.55 ✓
3573	4.6 ✓	6.1 ✓	1.5	49.37 ✓	3.15 ✓	5.10 ✓
3574	6.1 ✓	7.6 ✓	1.5	35.31 ✓	2.03 ✓	4.25 ✓
3575	7.6 ✓	9.1 ✓	1.5	32.23 ✓	1.98 ✓	3.70 ✓
3576	9.1 ✓	10.7 ✓	1.6	47.31 ✓	3.35 ✓	4.60 ✓
3577	10.7 ✓	12.2 ✓	1.5	25.37 ✓	1.80 ✓	2.88 ✓
3578	12.2 ✓	13.7 ✓	1.5	26.40 ✓	1.73 ✓	3.00 ✓
3579	13.7 ✓	15.2 ✓	1.5	29.14 ✓	1.75 ✓	4.23 ✓
3580	15.2 ✓	16.8 ✓	1.6	28.11 ✓	1.60 ✓	4.75 ✓
3581	16.8 ✓	18.3 ✓	1.5	85.72 ✓	6.55 ✓	9.33 ✓
3582	18.3 ✓	19.8 ✓	1.5	63.43 ✓	5.55 ✓	3.88 ✓
	19.8 ✓	24.5 ✓	4.7	NOT ASSAYED		
3583	24.5 ✓	26.4 ✓	1.9	49.03 ✓	3.30 ✓	3.25 ✓
	26.4 ✓	67.5 ✓	41.1	NOT ASSAYED		
3584	67.5 ✓	70.1 ✓	2.6	22.29 ✓	1.68 ✓	2.33 ✓
3585	70.1 ✓	71.6 ✓	1.5	70.63 ✓	4.83 ✓	5.20 ✓
3586	71.6 ✓	73.2 ✓	1.6	76.80 ✓	5.80 ✓	7.26 ✓
3587	73.2 ✓	74.7 ✓	1.5	78.86 ✓	6.40 ✓	8.75 ✓
3588	74.7 ✓	76.2 ✓	1.5	76.80 ✓	6.40 ✓	9.23 ✓
3589	76.2 ✓	77.7 ✓	1.5	69.60 ✓	5.65 ✓	8.40 ✓
3590	77.7 ✓	79.2 ✓	1.5	37.37 ✓	2.88 ✓	3.25 ✓
3591	79.2 ✓	80.8 ✓	1.6	77.83 ✓	4.85 ✓	8.87 ✓
3592	80.8 ✓	82.3 ✓	1.5	95.66 ✓	6.08 ✓	10.92 ✓
3593	82.3 ✓	83.8 ✓	1.5	102.86 ✓	7.80 ✓	11.69 ✓

LATITUDE  
DEPARTURE  
ELEVATION

DIP AT COLLAR  
BEARING  
LENGTH. 83.8 m (275 ft)

0.0 - 19.8 = 19.8 m (65 ft)

Ag 43.37 g/t.  
Pb 2.98 %  
Zn 4.57 %

0.0 - 26.4 = 26.4 m (86.6 ft)

Ag 36.06 g/t  
Pb 2.47 %  
Zn 3.77 %

LOW

70.1 - 83.8 = 13.7 m (45 ft)

Ag 76.28 g/t.  
Pb 5.63 %  
Zn 8.17 %

24.7.76 - 28.7.76

ASSAY NUMBER	SECTION		CORE LENGTH	ASSAYS		
	FROM (M)	TO (M)		Ag g/t	Pb %	Zn %
	0.0 ✓	5.0 ✓	5.0	8.00	0.00	0.00
4030	5.0 ✓	6.7 ✓	1.7	53.49 ✓	3.65 ✓	4.70 ✓
4031	6.7 ✓	8.7 ✓	2.0	10.63 ✓	4.20 ✓	4.15 ✓
4032	8.7 ✓	10.7 ✓	2.0	40.46 ✓	3.00 ✓	2.75 ✓
4033	10.7 ✓	12.7 ✓	2.0	38.40 ✓	2.98 ✓	2.10 ✓
4034	12.7 ✓	14.7 ✓	2.0	20.23 ✓	1.23 ✓	0.95 ✓
4035	14.7 ✓	16.7 ✓	2.0	21.26 ✓	1.38 ✓	1.13 ✓
4036	16.7 ✓	19.7 ✓	3.0	24.34 ✓	2.25 ✓	2.05 ✓
4037	19.7 ✓	22.7 ✓	3.0	23.31 ✓	2.30 ✓	1.75 ✓
4038	22.7 ✓	25.7 ✓	3.0	14.06 ✓	1.23 ✓	2.10 ✓
	25.7 ✓	53.9 ✓	28.2	NOT ASSAYED		
4039	53.9 ✓	55.9 ✓	2.0	7.20 ✓	0.33 ✓	0.70 ✓
4040	55.9 ✓	58.5 ✓	2.6	17.14 ✓	1.03 ✓	2.10 ✓
	58.5 ✓	68.5 ✓	10.0	NOT ASSAYED		
4041	68.5 ✓	70.5 ✓	2.0	5.14 ✓	0.23 ✓	0.50 ✓
4042	70.5 ✓	72.0 ✓	1.5	20.23 ✓	1.15 ✓	2.23 ✓
4043	72.0 ✓	73.5 ✓	1.5	26.40 ✓	1.60 ✓	2.40 ✓
4044	73.5 ✓	75.0 ✓	1.5	25.37 ✓	1.10 ✓	1.08 ✓
4045	75.0 ✓	76.5 ✓	1.5	76.80 ✓	2.23 ✓	4.20 ✓
4046	76.5 ✓	78.0 ✓	1.5	43.54 ✓	3.40 ✓	3.65 ✓
4047	78.0 ✓	79.5 ✓	1.5	55.54 ✓	3.80 ✓	6.76 ✓
4048	79.5 ✓	81.0 ✓	1.5	30.17 ✓	1.73 ✓	5.70 ✓
4049	81.0 ✓	82.5 ✓	1.5	28.46 ✓	1.65 ✓	3.58 ✓
4050	82.5 ✓	84.0 ✓	1.5	55.54 ✓	3.58 ✓	6.43 ✓
4051	84.0 ✓	85.5 ✓	1.5	88.80 ✓	5.25 ✓	10.06 ✓
4052	85.5 ✓	87.0 ✓	1.5	67.54 ✓	3.88 ✓	7.24 ✓
4053	87.0 ✓	89.0 ✓	2.0	42.51 ✓	2.45 ✓	2.75 ✓
4054	89.0 ✓	92.0 ✓	3.0	50.40 ✓	2.18 ✓	4.15 ✓
	92.0 ✓	121.3 ✓	29.3	NOT ASSAYED		
4055	121.3 ✓	122.8 ✓	1.5	97.72 ✓	6.82 ✓	10.10 ✓
4056	122.8 ✓	124.3 ✓	1.5	87.77 ✓	6.18 ✓	9.51 ✓
4057	124.3 ✓	125.8 ✓	1.5	55.54 ✓	3.10 ✓	6.17 ✓
4058	125.8 ✓	127.3 ✓	1.5	42.51 ✓	2.10 ✓	3.30 ✓
4059	127.3 ✓	128.8 ✓	1.5	39.43 ✓	1.73 ✓	1.98 ✓
4060	128.8 ✓	130.3 ✓	1.5	36.34 ✓	1.77 ✓	2.48 ✓
4061	130.3 ✓	131.8 ✓	1.5	79.54 ✓	4.25 ✓	5.15 ✓
4062	131.8 ✓	134.6 ✓	2.8	72.69 ✓	5.00 ✓	1.03 ✓
	134.6 ✓	142.3 ✓	7.7	0.00	0.00	0.00

LATITUDE S<sub>N</sub>

DIP AT COLLAR

DEPARTURE 160W

BEARING

ELEVATION

DEPTH

142.3 m (467 ft)

5.0 - 8.7 = 3.7 m (12 ft) Ag. 62.75 g/t

Pb 3.95% Zn 4.40%

15.0 - 32.0 = 17.0 m (56 ft)

Ag 53.28 g/t.

Pb 2.92%

Zn 5.26%

121.3 - 134.6 = 13.3 m (44 ft)

Ag 64.8 g/t.

Pb 4.00%

Zn 5.91%

3.7.76 - 4.7.76

ASSAY NUMBER	SECTION		CORE LENGTH	ASSAYS		
	From (m)	To (m)		Ag g/t	Pb %	Zn %
3594	0.0 ✓	3.0 ✓	3.0	25.37	1.75	1.08
	3.0 ✓	8.5 ✓	5.5	NOT ASSAYED		
3595	8.5 ✓	11.0 ✓	2.5	40.46	2.55	4.35
	11.0 ✓	18.0 ✓	7.0	NOT ASSAYED		
3596	18.0 ✓	19.5 ✓	1.5	45.26	3.25	6.17
3597	19.5 ✓	21.3 ✓	1.8	64.46	4.33	7.86
3598	21.3 ✓	22.9 ✓	1.6	54.51	3.80	6.95
3599	22.9 ✓	24.4 ✓	1.5	29.14	1.70	3.30
3600	24.4 ✓	25.9 ✓	1.5	24.34	1.78	2.03
3701	25.9 ✓	27.4 ✓	1.5	47.31	3.48	3.05
3702	27.4 ✓	29.0 ✓	1.6	59.31	4.13	3.15
3703	29.0 ✓	30.5 ✓	1.5	33.26	2.03	3.25
3704	30.5 ✓	32.0 ✓	1.5	10.97	1.18	1.40
3705	32.0 ✓	33.5 ✓	1.5	20.23	2.20	1.33
3706	33.5 ✓	34.7 ✓	1.2	16.11	1.43	1.66
3707	34.7 ✓	36.6 ✓	1.9	39.43	2.43	4.43
3708	36.6 ✓	37.8 ✓	1.2	54.51	3.45	6.00
	37.8 ✓	45.7 ✓	7.9	0.00	0.00	0.00

LATITUDE  
DEPARTURE  
ELEVATION

DIP AT COLLAR  
BEARING  
DEPTH. <sup>45.7</sup>~~115~~ m (150 ft)

8.5 - 11.0 = 2.5m (8.2 ft) Ag 40.46 g/t. Pb 2.55%. Zn 4.35%.

18.0 - 30.5 = 12.5m (41 ft)

Ag 45.37 g/t

Pb 2.97%

Zn 4.54%

18.0 - 37.8 = 19.8m (65 ft)

Ag 39.07 g/t

Pb 2.66%

Zn 3.96%

LOW

34.7 - 37.8 = 3.1m (10 ft) Ag 45.27 g/t

Pb 2.82% Zn 5.03%

25.7.76 - 26.7.76

ASSAY NUMBER	SECTION		CORE LENGTH	ASSAYS		
	FROM (M)	TO (M)		Ag g/t	Pb %	Zn %
3931	0.0 ✓	3.0 ✓	3.0	19.54 ✓	4.88 ✓	8.55 ✓
3932	3.0 ✓	4.6 ✓	1.6	90.86 ✓	5.26 ✓	8.80 ✓
3933	4.6 ✓	5.5 ✓	0.9	96.69 ✓	6.26 ✓	11.88 ✓
	5.5 ✓	15.4 ✓	9.9	NOT ASSAYED		
3937	15.4 ✓	16.8 ✓	1.4	12.69 ✓	4.80 ✓	6.63 ✓
	16.8 ✓	45.7 ✓	28.9	0.00	0.00	0.00

LATITUDE 2N  
DEPARTURE 70W  
ELEVATION

DIP AT COLLAR  
BEARING  
DEPTH

45.7m (150ft)

0.0 - 5.5 = 5.5m (18ft)

Ag. 85.64g/t Pb 5.22%  
Zn 9.17%

15.4 - 16.8 = 1.4m (4.6ft)

Ag. 12.69g/t Pb 4.80%  
Zn 6.63%

7.7.76 - 12.7.76

ASSAY NUMBER	SECTION		CORE LENGTH	ASSAYS		
	FROM (m)	TO (m)		Ag g/t	Pb %	Zn %
3709	0.0 ✓	15.0 ✓	15.0	6.00	0.00	0.00
	15.0 ✓	16.8 ✓	1.8	67.54	3.38	6.45
	16.8 ✓	43.5 ✓	26.7	NOT ASSAYED		
3710	43.5 ✓	44.6 ✓	1.1	27.43	1.85	3.05
	44.6 ✓	51.8 ✓	7.2	NOT ASSAYED		
3711	51.8 ✓	53.5 ✓	1.7	51.43	3.25	7.08
	53.5 ✓	62.0 ✓	8.5	NOT ASSAYED		
3712	62.0 ✓	64.0 ✓	2.0	59.31	3.93	4.65
3713	64.0 ✓	65.5 ✓	1.5	52.46	3.65	6.35
3714	65.5 ✓	67.1 ✓	1.6	15.09	1.05	1.55
3715	67.1 ✓	68.6 ✓	1.5	9.94	0.80	0.90
3716	68.6 ✓	70.1 ✓	1.5	13.03	0.83	1.73
3717	70.1 ✓	72.4 ✓	2.3	55.54	3.38	4.76
3718	72.4 ✓	76.2 ✓	3.8	17.14	0.78	1.25
	76.2 ✓	83.7 ✓	7.5	NOT ASSAYED		
3719	83.7 ✓	85.3 ✓	1.6	42.51	2.18	4.00
3720	85.3 ✓	86.9 ✓	1.6	55.54	2.78	4.76
3721	86.9 ✓	88.4 ✓	1.5	43.54	2.25	4.90
3722	88.4 ✓	89.9 ✓	1.5	58.63	2.65	4.46
3723	89.9 ✓	91.4 ✓	1.5	53.49	3.28	4.80
3724	91.4 ✓	93.0 ✓	1.6	35.31	2.10	3.10
3725	93.0 ✓	94.5 ✓	1.5	25.37	1.80	3.90
3726	94.5 ✓	96.0 ✓	1.5	32.23	2.33	4.46
3727	96.0 ✓	97.5 ✓	1.5	43.54	3.00	2.66
3728	97.5 ✓	99.1 ✓	1.6	32.23	2.13	2.70
3729	99.1 ✓	100.6 ✓	1.5	43.54	3.00	4.96
3730	100.6 ✓	102.1 ✓	1.5	39.43	2.88	3.16
3731	102.1 ✓	103.6 ✓	1.5	33.26	2.08	5.25
3732	103.6 ✓	105.2 ✓	1.6	9.94	0.65	3.10
3733	105.2 ✓	108.0 ✓	2.8	24.34	1.53	2.68
	108.0 ✓	132.5 ✓	24.5	0.00	0.00	0.00

LATITUDE 7N  
 DEPARTURE 76w.  
 ELEVATION

DIP AT COLLAR  
 BEARING  
 DEPTH 132.5 m (435 ft)

15.0 - 16.8 = 1.8 m (6 ft) Ag. 67.54 g/t. Pb. 3.38%. Zn. 6.45%

51.8 - 53.5 = 1.7 m (5.6 ft) Ag. 53.5 g/t. Pb. 3.25%. Zn. 7.08%

62.0 - 65.5 = 3.5 m (11.5 ft) Ag. 56.37 g/t.  
 Pb. 3.58%. Zn. 5.38%

70.1 - 72.4 = 2.3 m (7.5 ft) Ag. 55.54 g/t. Pb. 3.38%. Zn. 4.76%

83.7 - 91.4 = 7.7 m (25.3 ft)  
 Ag 50.70 g/t.  
 Pb 2.62%.  
 Zn 4.58%

83.7 - 103.6 = 19.9 m (65 ft)  
 Ag 41.43 g/t.  
 Pb 2.49%.  
 Zn 4.08%

99.1 - 103.6 = 4.5 m (14.75 ft)  
 Ag 38.74 g/t.  
 Pb 2.65%. Zn. 4.46%

26.7.76 - 28.7.76

ASSAY NUMBER	SECTION		CORE LENGTH	ASSAYS		
	FROM (m)	TO (m)		Ag g/t	Pb %	Zn %
3938	0.0	3.0	3.0	87.77	5.36	8.42
3939	3.0	4.6	1.6	88.80	4.38	9.28
3940	4.6	6.1	1.5	73.71	3.90	7.44
3941	6.1	7.6	1.5	83.66	4.18	7.89
3942	7.6	9.1	1.5	110.06	6.40	9.26
3943	9.1	10.7	1.6	75.77	4.25	9.26
3944	10.7	12.2	1.5	85.71	5.37	7.84
3945	12.2	13.7	1.5	60.34	3.08	5.80
3946	13.7	15.2	1.5	70.63	3.75	5.97
3947	15.2	16.8	1.6	83.66	4.83	8.52
3948	16.8	18.3	1.5	111.09	4.88	5.75
	18.3	47.2	28.9	NOT ASSAYED		
3949	47.2	48.8	1.6	161.49	9.71	18.51
3950	48.8	50.3	1.5	164.57	9.74	19.50
3951	50.3	51.8	1.5	111.09	7.10	15.43
3952	51.8	53.3	1.5	168.34	11.10	11.58
	53.3	54.4	1.1	NOT ASSAYED		
3953	54.4	56.4	2.0	75.77	4.70	5.45
3954	56.4	57.9	1.5	45.26	2.80	5.35
3955	57.9	59.4	1.5	62.40	4.48	9.56
3956	59.4	61.0	1.6	14.74	0.83	1.85
3957	61.0	62.5	1.5	8.91	0.20	0.98
3958	62.5	64.0	1.5	13.03	0.15	1.60
3959	64.0	67.1	3.1	15.09	0.10	0.68
3960	67.1	70.1	3.0	9.94	0.18	0.68
	70.1	93.0	22.9	NOT ASSAYED		
3961	93.0	95.8	2.8	23.34	2.15	3.05
	95.8	114.3	18.5	NOT ASSAYED		
3962	114.3	115.8	1.5	104.92	6.30	9.03
3963	115.8	117.6	1.8	40.46	3.13	3.45
	117.6	126.5	8.9	0.00	0.00	0.00

LATITUDE 2N  
DEPARTURE 10W  
ELEVATION

DIP AT COLLAR  
BEARING  
DEPTH 126.5 m (415 ft.)

0.0 - 18.3 m = 18.3 m (60 ft)

Ag 84.88 g/t.

Pb 4.64 %

Zn 7.84 %

47.2 - 59.4 = 12.2 m (40 ft)

Ag 101.43 g/t.

Pb 6.37 %

Zn 10.87 %

114.3 - 117.6 = 3.3 m (10.8 ft)

Ag 69.76 g/t. Pb 4.57 %

Zn 5.99 %

12.7.76 - 18.7.76.

ASSAY NUMBER	SECTION		CORE LENGTH	ASSAYS		
	FROM (m)	TO (m)		Ag g/t	Pb %	Zn %
3734	0.0	4.6	4.6	20.57	0.13	0.20
3735	4.6	7.0	2.4	5.14	0.30	0.56
	7.0	29.0	22.0	NOT ASSAYED		
3736	29.0	30.5	1.5	58.63	4.10	2.20
3737	30.5	32.0	1.5	44.23	3.35	1.60
3738	32.0	33.5	1.5	34.29	2.75	2.10
3739	33.5	35.1	1.6	25.37	1.99	0.85
3740	35.1	36.6	1.5	25.37	1.98	1.46
3741	36.6	38.1	1.5	18.17	1.55	0.80
3742	38.1	39.6	1.5	2.06	0.23	0.18
3743	39.6	41.1	1.5	9.94	0.93	0.63
3744	41.1	42.7	1.6	33.26	2.90	1.00
3745	42.7	44.2	1.5	20.23	1.65	3.38
3746	44.2	47.2	3.0	3.09	0.30	0.80
3747	47.2	50.3	3.1	8.23	0.73	1.20
3748	50.3	53.3	3.0	10.97	1.00	1.56
3749	53.3	54.9	1.6	9.94	0.85	0.96
3750	54.9	56.4	1.5	22.29	1.35	2.90
3751	56.4	57.9	1.5	33.26	2.28	3.30
3752	57.9	59.4	1.5	40.46	2.98	2.40
3753	59.4	61.0	1.6	78.86	5.94	8.11
3754	61.0	62.5	1.5	65.49	4.43	6.24
3755	62.5	64.0	1.5	58.63	3.65	7.18
3756	64.0	65.7	1.7	16.11	0.80	1.80
	65.7	85.3	19.6	NOT ASSAYED		
3757	85.3	89.9	4.6	55.54	4.20	4.56
3758	89.9	99.1	9.2	43.54	3.13	6.10

low

LATITUDE 3N  
DEPARTURE 16W  
ELEVATION

DIP AT COLLAR  
BEARING  
LENGTH 99.1 m (325 ft)

59.4 - 64.0 = 4.6 m (15 ft)  
Ag. 67.9 g/t. Pb 4.70%.  
Zn 7.19%.

85.3 - 99.1 = 13.8 m (46 ft)  
Ag. 47.54 g/t. Pb 3.49%.  
Zn 5.59%.

27.7.76 - 4.8.76

ASSAY NUMBER	SECTION		CORE LENGTH	ASSAYS		
	FROM (m)	TO (m)		Ag %	Pb %	Zn %
3964	0.0 ✓	1.5 ✓	1.5	17.83 ✓	5.27 ✓	8.10 ✓
3965	1.5 ✓	3.5 ✓	2.0	55.54 ✓	4.05 ✓	6.78 ✓
	3.5 ✓	43.5 ✓	40.0	NOT ASSAYED		
3966	43.5 ✓	45.7 ✓	2.2	125.14 ✓	6.26 ✓	10.87 ✓
3967	45.7 ✓	48.2 ✓	2.5	82.63 ✓	5.00 ✓	7.71 ✓
	48.2 ✓	49.5 ✓	1.3	NOT ASSAYED		
3968	49.5 ✓	51.8 ✓	2.3	17.14 ✓	0.20 ✓	0.03 ✓
	51.8 ✓	55.0 ✓	3.2	NOT ASSAYED		
3969	55.0 ✓	57.9 ✓	2.9	52.46 ✓	3.35 ✓	4.75 ✓
3970	57.9 ✓	59.4 ✓	1.5	57.60 ✓	3.35 ✓	5.15 ✓
3971	59.4 ✓	61.0 ✓	1.6	76.80 ✓	4.33 ✓	1.84 ✓
3972	61.0 ✓	62.5 ✓	1.5	61.37 ✓	3.98 ✓	5.20 ✓
	62.5 ✓	64.5 ✓	2.0	NOT ASSAYED		
3973	64.5 ✓	67.2 ✓	2.7	22.28 ✓	1.73 ✓	2.13 ✓
	67.2 ✓	68.9 ✓	1.7	NOT ASSAYED		
3974	68.9 ✓	71.6 ✓	2.7	8.91 ✓	0.81 ✓	1.25 ✓
3975	71.6 ✓	74.3 ✓	2.7	3.09 ✓	0.33 ✓	0.50 ✓
	74.3 ✓	82.0 ✓	7.7	NOT ASSAYED		
3976	82.0 ✓	83.8 ✓	1.8	13.03 ✓	0.98 ✓	2.00 ✓
3977	83.8 ✓	86.9 ✓	3.1	7.20 ✓	0.68 ✓	1.28 ✓
	86.9 ✓	105.3 ✓	18.4	NOT ASSAYED		
3978	105.3 ✓	108.2 ✓	2.9	65.49 ✓	3.45 ✓	5.15 ✓
3979	108.2 ✓	111.3 ✓	3.1	29.14 ✓	2.10 ✓	3.65 ✓
	111.3 ✓	125.5 ✓	14.2	NOT ASSAYED		
3997	125.5 ✓	128.5 ✓	3.0	10.97 ✓	0.53 ✓	1.00 ✓
3998	128.5 ✓	131.5 ✓	3.0	5.14 ✓	0.25 ✓	0.13 ✓
	131.5 ✓	134.2 ✓	2.7	NOT ASSAYED		
3999	134.2 ✓	135.6 ✓	1.4	96.69 ✓	1.02 ✓	8.07 ✓
4000	135.6 ✓	137.3 ✓	1.7	63.43 ✓	4.20 ✓	8.25 ✓
4081	137.3 ✓	138.7 ✓	1.4	34.29 ✓	2.15 ✓	4.45 ✓
4082	141.7 ✓	141.7 ✓	3.0	2.06 ✓	0.05 ✓	TR ✓
4083	144.8 ✓	144.8 ✓	3.1	20.23 ✓	1.28 ✓	1.50 ✓
	144.8 ✓	169.5 ✓	24.7	NOT ASSAYED		
4084	169.5 ✓	172.2 ✓	2.7	38.40 ✓	2.08 ✓	3.85 ✓
4085	172.2 ✓	173.7 ✓	1.5	90.86 ✓	5.66 ✓	8.04 ✓
4086	173.7 ✓	175.3 ✓	1.6	53.49 ✓	4.15 ✓	4.25 ✓
4087	175.3 ✓	176.8 ✓	1.5	25.37 ✓	1.30 ✓	1.33 ✓
4088	176.8 ✓	178.3 ✓	1.5	18.17 ✓	2.13 ✓	1.20 ✓
4089	178.3 ✓	179.8 ✓	1.5	24.34 ✓	1.93 ✓	1.85 ✓
4090	179.8 ✓	181.4 ✓	1.6	51.43 ✓	2.83 ✓	2.35 ✓
4091	181.4 ✓	182.9 ✓	1.5	54.51 ✓	3.35 ✓	3.05 ✓
4092	182.9 ✓	184.4 ✓	1.5	40.46 ✓	2.60 ✓	2.35 ✓
4093	184.4 ✓	186.0 ✓	1.6	22.29 ✓	1.13 ✓	1.18 ✓
	186.0 ✓	190.5 ✓	4.5	0.00 ✓	0.00 ✓	0.00 ✓

LATITUDE TN

DIP AT COLLAR

DEPARTURE 80W.

BEARING

ELEVATION

DEPTH: 190.5 m (625 ft).

0.0 - 3.5 m = 3.5 m (11.5 ft) Ag. 65.09 g/t

Pb 4.57%, Zn 7.35%

13.5 - 48.2 m = 4.7 m (15.5 ft) Ag. 102.53 g/t

Pb 5.59%, Zn 9.91%

55.0 - 62.5 = 7.5 m (24.5 ft)

Ag 60.46 g/t.

Pb 3.69%

Zn 5.58%

105.3 - 111.3 = 6.0 m (19.7 ft) Ag. 46.71 g/t.

Pb 2.75%, Zn 4.38%

134.2 - 138.7 = 4.5 m (15 ft) Ag. 64.71 g/t

Pb 4.44%

Zn 7.01%

169.5 - 175.3 = 5.8 m (19 ft) Ag 56.13 g/t.

Pb 3.58%

Zn 5.04%

(201)

29.7.76 - 30.7.76

ASSAY NUMBER	SECTION		CORE LENGTH	ASSAYS		
	FROM (M)	TO (M)		Ag g/t	Pb %	Zn %
4065	0.0 32.0	32.0 33.5	32.0 1.5	0.00 15.77	0.00 5.76	0.00 5.40
4066	33.5	35.1	1.6	12.69	5.36	5.45
	35.1	39.0	3.9	NOT ASSAYED		
4067	39.0	41.1	2.1	52.46	2.55	1.90
4068	41.1	42.7	1.6	70.63	3.95	2.45
4069	42.7	45.7	3.0	103.87	7.15	7.13
4070	45.7	48.8	3.1	100.80	6.40	6.53
4071	48.8	50.3	1.5	104.92	7.36	7.79
4072	50.3	51.8	1.5	95.66	6.10	6.63
4073	51.8	53.3	1.5	89.93	7.06	6.75
4074	53.3	54.9	1.6	60.34	4.45	3.75
4075	54.9	56.4	1.5	25.37	1.70	1.23
4076	56.4	57.9	1.5	32.23	1.93	1.00
4077	57.9	59.4	1.5	34.29	2.05	1.25
4078	59.4	61.5	2.1	35.31	1.85	1.40
	61.5	76.2	14.7	0.00	0.00	0.00

WAGITUDE 2N

DIP AT COLLAR +48°

DEPARTURE 70W

BEARING 224°

ELEVATION

DEPTH 76.2 m (250 ft)

32.0 - 35.1 = 3.1 m (10 ft) Ag 74.18 g/t

Pb 5.55% Zn 5.43%

41.1 - 54.9 = 13.8 m (45 ft)

Ag 91.99 g/t

Pb 6.2 %

Zn 6.04 %

(E.C.J.)

30.7.76 - 1.8.76

ASSAY NUMBER	SECTION		CORE LENGTH	ASSAYS		
	FROM (M)	TO (M)		Ag g/t	Pb %	Zn %
	0.0	61.0	61.0	0.00	0.00	0.00

NO INTERSECTIONS -

LATITUDE 2N

DEPARTURE 70W

ELEVATION

DIP AT COLLAR +65°

BEARING 44°

LENGTH 61m (200ft)

(E.C.)

29.7.76 - 6.8.76

ASSAY NUMBER	SECTION		CORE LENGTH	ASSAYS		
	FROM (M)	TO (M)		Ag g/t	Pb %	Zn %
4079	0.0 ✓	3.9 ✓	3.9	18.17 ✓	1.07 ✓	1.43 ✓
	3.9 ✓	6.2 ✓	2.3	NOT ASSAYED		
4080	6.2 ✓	7.5 ✓	1.3	36.34 ✓	2.28 ✓	3.25 ✓
	7.5 ✓	30.7 ✓	23.2	NOT ASSAYED		
3988	30.7 ✓	33.8 ✓	3.1	14.06 ✓	1.25 ✓	1.08 ✓
3989	33.8 ✓	36.6 ✓	2.8	16.11 ✓	1.03 ✓	1.18 ✓
3990	36.6 ✓	39.8 ✓	3.2	37.37 ✓	2.80 ✓	2.45 ✓
3991	39.8 ✓	42.7 ✓	2.9	17.14 ✓	1.08 ✓	0.45 ✓
	42.7 ✓	46.0 ✓	3.3	NOT ASSAYED		
3992	46.0 ✓	49.0 ✓	3.0	26.40 ✓	2.38 ✓	1.05 ✓
3993	49.0 ✓	52.1 ✓	3.1	15.09 ✓	1.00 ✓	1.35 ✓
3994	52.1 ✓	55.1 ✓	3.0	23.31 ✓	1.93 ✓	0.63 ✓
	55.1 ✓	56.6 ✓	1.5	NOT ASSAYED		
3995	56.6 ✓	59.7 ✓	3.1	27.43 ✓	1.85 ✓	1.95 ✓
3996	59.7 ✓	63.0 ✓	3.3	8.23 ✓	0.54 ✓	0.53 ✓
	63.0 ✓	77.0 ✓	14.0	NOT ASSAYED		
4101	77.0 ✓	79.5 ✓	2.5	25.37 ✓	1.14 ✓	1.68 ✓
4102	79.5 ✓	81.0 ✓	1.5	13.03 ✓	0.09 ✓	0.23 ✓
4103	81.0 ✓	82.6 ✓	1.6	38.40 ✓	2.65 ✓	3.45 ✓
4104	82.6 ✓	84.1 ✓	1.5	29.14 ✓	1.90 ✓	3.20 ✓
4105	84.1 ✓	85.6 ✓	1.5	4.11 ✓	0.35 ✓	0.63 ✓
	85.6 ✓	107.5 ✓	21.9	NOT ASSAYED		
4106	107.5 ✓	109.0 ✓	1.5	61.37 ✓	4.25 ✓	8.23 ✓
4107	109.0 ✓	110.5 ✓	1.5	13.03 ✓	0.90 ✓	1.10 ✓
4108	110.5 ✓	112.0 ✓	1.5	9.94 ✓	0.65 ✓	1.08 ✓
4109	112.0 ✓	113.5 ✓	1.5	8.23 ✓	0.58 ✓	1.45 ✓
4110	113.5 ✓	117.6 ✓	4.1	14.06 ✓	1.13 ✓	2.10 ✓
	117.6 ✓	122.2 ✓	4.6	0.00	0.00	0.00

LATITUDE 3N  
 DEPARTURE 76W  
 ELEVATION

DIP AT COLLAR -50°  
 BEARING 44°  
 LENGTH 122.2m (401ft)

107.5 - 109.0 = 1.5m (5ft) Ag 61.37g/t Pb 4.25% Zn 8.23%

ECJ.

1.8.76 - 2.8.76

ASSAY NUMBER	SECTION		CORE LENGTH	ASSAYS		
	FROM (m)	TO (m)		Ag g/t	Pb %	Zn %
3980	0.0 ✓ 37.0 ✓	37.0 ✓ 39.6 ✓	37.0 2.4	86.74 ✓ 0.00	6.35 ✓ 0.00	6.50 ✓ 0.00
3981	39.6 ✓	41.1 ✓	1.5	86.34 ✓	2.58 ✓	0.15 ✓
3982	41.1 ✓	42.7 ✓	1.6	65.49 ✓	3.70 ✓	3.40 ✓
3983	42.7 ✓	44.2 ✓	1.5	82.63 ✓	5.97 ✓	5.15 ✓
3984	44.2 ✓	47.0 ✓	2.8	59.31 ✓	4.55 ✓	3.77 ✓
	47.0 ✓	64.5 ✓	17.5	NOT ASSAYED		
3985	64.5 ✓	67.5 ✓	3.0	54.51 ✓	4.10 ✓	3.25 ✓
	67.5 ✓	76.2 ✓	4.7	0.00	0.00	0.00

LATITUDE 20  
DEPARTURE 200  
ELEVATION

DIP AT COLLAR +75°  
BEARING 224°  
DEPTH 76.2 m (250 ft)

$37.0 - 47.0 = 10.0 \text{ m (33 ft)}$

Ag 65.75 g/t  
Pb 4.67%  
Zn 4.04%

$64.5 - 67.5 = 3.0 \text{ m (10 ft)}$  Ag 54.51 g/t  
Pb 4.10% Zn 3.25%

5.8.76 - 16.8.76

ASSAY NUMBER	SECTION		CORE LENGTH	ASSAYS		
	FROM (M)	TO (M)		Ag g/t	Pb %	Zn %
4094	0.0	3.0	3.0	63.43	4.08	8.19
	3.0	55.8	52.8	NOT ASSAYED		
4095	55.8	56.8	1.0	114.86	7.05	16.64
	56.8	59.8	3.0	NOT ASSAYED		
4096	59.8	62.5	2.7	77.83	5.48	7.84
	62.5	83.4	20.9	NOT ASSAYED		
4097	83.4	86.4	3.0	58.63	0.88	1.46
4098	86.4	87.5	1.1	16.11	3.98	5.20
	87.5	98.0	10.5	NOT ASSAYED		
4099	98.0	100.0	2.0	53.49	3.63	6.53
	100.0	100.6	0.6	NOT ASSAYED		
4100	100.6	102.1	1.5	17.14	0.91	0.80
4201	102.1	104.3	2.2	5.14	0.35	0.53
	104.3	123.4	19.1	0.00	0.00	0.00

LATITUDE 7N  
DEPARTURE 80W  
ELEVATION

DIP AT COLLAR -60°  
BEARING 44°  
LENGTH 123.4m (405ft)

0.0 - 3.0m = 3.0m (10ft) Ag. 63.43g/t. Pb. 4.08%. Zn 8.19%

55.8 - 62.5 = 6.7m (22ft)

Ag. 48.51g/t. Pb 3.26%. Zn 5.64%

86.4 - 87.5 = 1.1m (3.6ft) Ag. 16.11g/t. Pb. 3.98%. Zn 5.20%

98.0 - 100.0 = 2.0m (6.6ft) Ag 53.49g/t. Pb. 3.63%. Zn 6.53%

E.C.J.

5.8.76 - 8.8.76

ASSAY NUMBER	SECTION		CORE LENGTH	ASSAYS		
	FROM (M)	TO (M)		Ag g/t	Pb %	Zn %
4111	0.0 ✓	3.0 ✓	3.0	20.23	0.58	1.45
4112	3.0 ✓	4.6 ✓	1.6	12.00	0.18	1.33
4113	4.6 ✓	6.1 ✓	1.5	25.37	0.60	0.85
4114	6.1 ✓	7.6 ✓	1.5	12.00	0.45	1.35
4115	7.6 ✓	9.1 ✓	1.5	54.51	4.65	6.03
4116	9.1 ✓	10.7 ✓	1.6	106.97	7.64	13.31
4117	10.7 ✓	12.2 ✓	1.5	122.06	9.64	13.74
4118	12.2 ✓	13.7 ✓	1.5	106.97	7.11	11.16
4119	13.7 ✓	15.2 ✓	1.5	89.83	6.40	11.44
4120	15.2 ✓	16.8 ✓	1.6	106.97	7.36	10.92
4121	16.8 ✓	18.3 ✓	1.5	55.54	4.48	3.56
4122	18.3 ✓	19.8 ✓	1.5	70.63	5.56	4.68
4123	19.8 ✓	21.3 ✓	1.5	94.63	6.64	6.22
4124	21.3 ✓	24.0 ✓	2.7	84.69	5.99	7.62
	24.0 ✓	59.8 ✓	35.8	NOT ASSAYED		
4125	59.8 ✓	61.3 ✓	1.5	86.74	5.51	9.25
4126	61.3 ✓	62.7 ✓	1.4	75.77	4.45	8.64
	62.7 ✓	96.3 ✓	33.6	0.00	0.00	0.00

LATITUDE 2N  
DEPARTURE 66W.  
ELEVATION

DIP AT COLLAR 0°  
BEARING 224°  
LENGTH 96.3 m (316 ft)

$7.6 - 24.0 = 16.4 \text{ m (54 ft)}$

Ag. 89.16 g/t  
Pb 6.52 %  
Zn 8.82 %

$59.8 - 62.7 = 2.9 \text{ m (9.5 ft)}$

Ag 81.44 g/t Pb 5.00 %  
Zn 8.96 %

9.8.76 - 11.8.76

ASSAY NUMBER	SECTION		CORE LENGTH	ASSAY		
	FROM (M)	TO (M)		Ag g/t	Pb %	Zn %
4202	0.0 ✓	2.1 ✓	2.1	190.63 ✓	10.76 ✓	14.99 ✓
4203	2.1 ✓	4.5 ✓	2.4	141.26 ✓	8.44 ✓	10.61 ✓
4204	4.5 ✓	6.1 ✓	1.6	33.26 ✓	1.98 ✓	3.05 ✓
4205	6.1 ✓	7.6 ✓	1.5	100.80 ✓	6.66 ✓	10.56 ✓
4206	7.6 ✓	9.1 ✓	1.5	58.29 ✓	3.93 ✓	7.14 ✓
4207	9.1 ✓	11.7 ✓	2.6	73.71 ✓	4.60 ✓	7.46 ✓
	11.7 ✓	21.3 ✓	9.6	NOT ASSAYED		
4208	21.3 ✓	22.9 ✓	1.6	7.20 ✓	0.25 ✓	0.15 ✓
4209	22.9 ✓	24.4 ✓	1.5	44.23 ✓	2.48 ✓	6.25 ✓
4210	24.4 ✓	25.9 ✓	1.5	106.97 ✓	4.58 ✓	10.66 ✓
4211	25.9 ✓	27.4 ✓	1.5	28.11 ✓	1.68 ✓	3.55 ✓
4212	27.4 ✓	29.0 ✓	1.6	14.06 ✓	0.65 ✓	0.83 ✓
4213	29.0 ✓	30.5 ✓	1.5	9.94 ✓	0.53 ✓	0.60 ✓
4214	30.5 ✓	33.5 ✓	3.0	15.09 ✓	0.73 ✓	0.73 ✓
4215	33.5 ✓	36.6 ✓	3.1	7.89 ✓	0.33 ✓	0.15 ✓
4216	36.6 ✓	39.6 ✓	3.0	8.91 ✓	0.33 ✓	0.70 ✓
4217	39.6 ✓	41.1 ✓	1.5	72.69 ✓	3.80 ✓	8.23 ✓
4218	41.1 ✓	42.7 ✓	1.6	76.80 ✓	4.18 ✓	9.60 ✓
4219	42.7 ✓	44.2 ✓	1.5	68.57 ✓	4.05 ✓	8.40 ✓
4220	44.2 ✓	45.7 ✓	1.5	93.94 ✓	5.25 ✓	10.66 ✓
4221	45.7 ✓	47.2 ✓	1.5	114.86 ✓	5.92 ✓	14.33 ✓
4222	47.2 ✓	48.8 ✓	1.6	16.11 ✓	0.75 ✓	2.55 ✓
4223	48.8 ✓	50.3 ✓	1.5	36.34 ✓	1.90 ✓	5.65 ✓
4224	50.3 ✓	51.8 ✓	1.5	109.03 ✓	5.67 ✓	12.95 ✓
4225	51.8 ✓	53.3 ✓	1.5	103.89 ✓	6.56 ✓	14.47 ✓
4226	53.3 ✓	54.9 ✓	1.6	164.57 ✓	8.76 ✓	20.63 ✓
4227	54.9 ✓	56.4 ✓	1.5	81.60 ✓	5.81 ✓	7.29 ✓
4228	56.4 ✓	57.9 ✓	1.5	34.29 ✓	2.28 ✓	2.55 ✓
4229	57.9 ✓	59.6 ✓	1.7	30.17 ✓	1.50 ✓	4.60 ✓
	59.6 ✓	67.0 ✓	7.4	NOT ASSAYED		
4230,	67.0 ✓	70.2 ✓	3.2	36.34 ✓	2.24 ✓	4.45 ✓
	70.2 ✓	97.0 ✓	26.8	NOT ASSAYED		

DDH A 142 CONTINUED ON  
PAGES 104 & 105.

LATITUDE 7N

DIP AT COLLAR  $-30^{\circ}$ 

DEPARTURE 80W

BEARING  $224^{\circ}$ 

ELEVATION

LENGTH 152.4 m. (500 ft).

$$0.0 - 11.7 = 11.7 \text{ m (38 ft)}$$

Ag 104.52 g/t

Pb 6.31 %

Zn 9.21 %

$$22.9 - 25.9 = 3.0 \text{ m (10 ft)} \cdot \text{Ag } 75.6 \text{ g/t}$$

Pb 3.53% Zn 8.46%

$$39.6 - 56.4 = 16.8 \text{ m (55 ft)}$$

Ag 85.32 g/t

Pb 4.78 %

Zn 10.44 %

$$67.0 - 70.2 = 3.2 \text{ m (10.5 ft)}$$

Ag 36.34 g/t, Pb 2.24 %

Zn 4.45 %

now

ASSAY NUMBER	SECTION		CORE LENGTH	ASSAYS		
	FROM (M)	TO (M)		Ag g/t	Pb %	Zn %
4231	97.0	99.1	2.1	15.09	0.90	1.45
4232	99.1	100.6	1.5	9.94	0.55	1.03
4233	100.6	102.1	1.5	14.06	0.70	0.90
4234	102.1	103.6	1.5	13.03	0.63	0.98
4235	103.6	105.2	1.6	26.40	1.94	1.63
4236	105.2	106.7	1.5	58.63	5.20	1.70
4237	106.7	108.2	1.5	22.29	0.80	0.90
4238	108.2	109.7	1.5	20.23	0.05	0.23
4239	109.7	111.3	1.6	18.17	0.05	0.30
4240	111.3	112.8	1.5	8.91	0.08	0.25
4241	112.8	114.3	1.5	48.34	3.30	4.18
4242	114.3	115.8	1.5	8.23	0.04	0.20
4243	115.8	117.3	1.5	46.29	2.63	4.15
4244	117.3	118.9	1.6	64.46	4.00	6.38
4245	118.9	120.4	1.5	25.37	2.13	4.05
4246	120.4	121.9	1.5	45.26	2.38	4.30
4247	121.9	123.4	1.5	70.63	5.20	8.89
4248	123.4	125.0	1.6	91.89	6.69	12.04
4249	125.0	126.5	1.5	71.66	4.65	8.13
4250	126.5	128.7	2.2	64.46	3.78	8.43
	128.7	152.4	23.7	0.00	0.00	0.00

LATITUDE  
DEPARTURE  
ELEVATION

DIP AT COLLAR  
BEARING  
LENGTH

105.2 - 106.7 = 1.5m (5ft) Ag 58.63 g/t,  
Pb 5.20%, Zn 1.70%

LOW

112.8 - 128.7 = 15.9m (52ft)

Ag 54.54 g/t.  
Pb 4.48%  
Zn 6.21%

RDH U 143

Assay	Section	Core	Assays
-------	---------	------	--------

Number from (m) / 10 (m) length  
 Pb %  
 Ag %  
 Zn %

4127	0.0	4.0	4.0	0.18	0.63
4128	4.6	7.6	8.0	5.14	0.43
4129	7.6	10.3	2.7	7.20	0.45
4130	10.3	13.4	3.1	4.11	0.10
4131	13.4	16.8	3.4	28.11	0.23
4132	16.8	19.8	3.0	7.89	0.23
4133	19.8	22.9	3.1	5.14	0.15
4134	22.9	25.9	3.0	7.89	0.13
4135	25.9	29.0	3.1	2.06	0.03
4136	29.0	32.0	3.2	7.22	0.22
4137	32.0	35.1	3.1	15.09	0.48
4138	35.1	38.1	3.0	5.14	0.10
4139	38.1	42.7	4.6	5.14	0.18

42.7 / 76.8 / 34.1  
 NOT ASSAYED

4140	76.8	79.2	2.4	20.23	1.42	2.13
4141	80.8	82.3	1.6	45.26	2.05	2.50

80.8 / 82.3 / 1.5  
 NOT ASSAYED

4142	82.3	85.3	1.5	48.34	3.42	2.85
4143	85.3	88.4	1.5	100.82	7.75	8.86
4144	88.4	91.4	1.6	63.43	6.42	4.55
4145	91.4	94.5	1.5	47.31	4.32	3.65
4251	94.5	97.5	1.5	9.94	0.90	0.93
4146	97.5	100.6	1.5	6.17	0.18	0.35
4147	100.6	103.7	1.6	20.23	1.43	1.90
4148	103.7	106.8	1.5	32.23	2.90	3.40
4149	106.8	109.9	1.5	35.31	3.10	2.10
4150	109.9	113.0	1.5	8.23	0.40	0.08

4151	113.0	116.1	1.6	68.57	5.93	6.93
4152	116.1	119.2	1.5	47.54	4.32	7.46
4153	119.2	122.3	1.5	42.51	3.08	6.52
4154	122.3	125.4	3.1	9.94	0.68	0.84
4155	125.4	128.5	3.0	8.91	0.43	0.60
4156	128.5	131.6	3.1	10.97	1.03	1.15
4157	131.6	134.7	3.0	8.23	0.55	1.03
4158	134.7	137.8	3.0	18.17	1.08	0.70
4159	137.8	140.9	3.1	7.20	0.28	0.40
4160	140.9	144.0	3.0	4.11	0.18	0.50
4161	144.0	147.1	3.1	3.09	0.30	0.60

126.5	129.6	132.7	1.61	0.00	0.00	0.00
129.6	132.7	135.8	3.1	3.09	0.30	0.60

LATITUDE 2N

DEPARTURE 66W

ELEVATION

DIP AT COLLAR  $-25^{\circ}$ BEARING  $044^{\circ}$ DEPTH  $136.6\text{ m}$  (~~448~~  $435\text{ ft}$ ).

$$82.3 - 88.4 = 6.1\text{ m (20 ft)}$$

Ag 64.94 g/t.

Pb 5.48%

Zn 4.97%

$$93.0 - 96.0 = 3.0\text{ m (10 ft)} \quad \text{Ag } 33.77\text{ g/t}$$

Pb = 3.0%    Zn 2.75%

LOW

$$97.5 - 102.1 = 4.6\text{ m (15 ft)} \quad \text{Ag } 59.74\text{ g/t}$$

Pb 4.50%

Zn 6.98%

DDH U 144 ✓

12.8.76 - 13.8.76

ASSAY NUMBER	SECTION		CORE LENGTH	ASSAYS		
	FROM (m)	TO (m)		Ag g/t	Pb %	Zn %
4252	0.0	57.3	57.3	0.00	0.00	0.00
	57.3	59.4	2.1	48.34	3.15	6.65
4253	59.4	61.3	1.9	74.74	5.18	1.16
	61.3	64.3	3.0	NO ASSAYED		
4254	64.3	65.9	1.6	27.43	2.05	3.10
	65.9	73.2	7.3	0.00	0.00	0.00

LATITUDE TN

DIP AT COLLAR +50°

DEPARTURE 80W.

BEARING 44°

ELEVATION

DEPTH 73.2 m (240 ft)

57.3 - 61.3 = 4.0m (13ft) Ag. 60.88 g/t

Pb. 4.08% Zn. 6.89%

ASSAY NUMBER.	SECTION		CORE LENGTH	ASSAYS		
	FROM (m)	TO (m)		Ag g/t	Pb %	Zn %
4162	0.0	4.6	4.6	6.17	0.08	0.90
4163	4.6	7.6	3.0	5.14	0.07	1.28
4164	7.6	10.7	3.1	9.94	0.35	1.68
4165	10.7	13.7	3.0	14.06	0.25	0.70
4166	13.7	16.8	3.1	6.17	0.05	0.43
4167	16.8	19.8	3.0	6.17	0.18	0.85
4168	19.8	22.9	3.1	7.20	0.13	0.53
22.9 38.3 15.4 NOT ASSAYED						
4169	38.3	42.7	4.4	3.06	0.04	0.35
4170	42.7	45.7	3.0	5.14	0.04	0.45
4171	45.7	47.2	1.5	15.09	0.75	2.75
4172	47.2	48.8	1.6	18.17	0.90	2.58
4173	48.8	50.3	1.5	30.17	2.60	3.55
4174	50.3	51.8	1.5	30.17	1.65	2.23
51.8 90.5 38.7 NOT ASSAYED						
4175	90.5	93.0	2.5	54.51	3.30	5.94
4176	93.0	94.5	1.5	38.40	2.48	4.10
94.5 97.5 3.0 NOT ASSAYED						
4177	97.5	99.1	1.6	20.23	1.38	1.88
4178	99.1	100.6	1.5	27.43	2.40	2.20
4179	100.6	102.1	1.5	19.20	1.50	0.75
4180	102.1	103.6	1.5	9.94	0.63	1.08
4181	103.6	106.7	3.1	42.51	2.65	4.25
	106.7	121.9	15.2	0.00	0.00	0.00

LATITUDE 2N.  
 DEPARTURE 66W.  
 ELEVATION

DIP AT COLLAR. -65°  
 BEARING 044°  
 DEPTH 121.9 m (400 ft).

90.5 - 94.5 = 4.0 m (13 ft) Ag. 48.47 g/t.  
 Pb. 3.46% Zn 5.25%

103.6 - 106.7 = 3.1 m (10 ft) Ag. 42.51 g/t.  
 Pb. 2.65% Zn 4.25% LOW

E.C.J.

DDH U 146 ✓

13.8.76 - 15.8.76

ASSAY NUMBER	SECTION		CORE LENGTH	ASSAYS		
	FROM (m)	TO (m)		Ag g/t	Pb %	Zn %
	0.0	15.2	15.2	0.00	0.00	0.00
4255	15.2	18.3	3.1	24.34	1.30	2.10
4256	18.3	21.3	3.0	24.34	1.10	1.55
4257	21.3	22.9	1.6	26.40	1.43	2.13
4258	22.9	24.4	1.5	28.46	1.93	2.80
4259	24.4	25.9	1.5	45.26	3.30	4.60
4260	25.9	27.4	1.5	21.26	1.40	3.40
4261	27.4	29.0	1.6	77.83	5.49	7.16
4262	29.0	30.5	1.5	49.87	3.20	6.00
4263	30.5	32.3	1.8	70.63	4.23	5.66
	32.3	39.0	6.7	NOT ASSAYED		
4264	39.0	41.6	2.6	38.40	2.35	4.25
	41.6	44.0	2.4	NOT ASSAYED		
4265	44.0	45.7	1.7	35.31	1.90	3.68
4266	45.7	47.2	1.5	35.31	1.68	1.18
4267	47.2	49.1	1.9	65.49	3.90	5.20
	49.1	73.7	24.6	0.00	0.00	0.00

LATITUDE 7N  
DEPARTURE 80W  
ELEVATION.

DIP AT COLLAR +90°  
BEARING  
DEPTH 73.7m (242 ft)

24.4 - 32.3 = 7.9m (26ft)

Ag 49.82 g/t

Pb 3.56%

Zn 5.40%

27.4 - 32.3 = 4.9m (16ft)

Ag 66.47 g/t Pb 4.33%

Zn 6.25%

39.0 - 41.6 = 2.6m (8.5ft) Ag 38.40 g/t

LOW

Pb 2.35% Zn 4.25%

44.0 - 49.1 = 5.1m (16 3/4 ft)

47.2 - 49.1 = 1.9m (6ft) Ag 65.49 Ag 46.55 g/t Pb 2.58%

Pb 3.90% Zn 5.20%

Zn 3.51%

E.O.J.

DDH U 147 ✓

15.8.76 - 18.8.76

ASSAY NUMBER	SECTION		CORE LENGTH	ASSAYS		
	FROM (M)	TO (M)		Ag g/t	Pb %	Zn %
4268	0.0	6.1	6.1	5.14	0.17	2.23
4269	6.1	9.1	3.0	7.20	0.13	0.88
4270	9.1	12.2	3.1	10.97	0.18	1.15
4271	12.2	15.2	3.0	7.20	0.10	0.93
4272	15.2	18.3	3.1	8.23	0.13	0.80
4273	18.3	19.8	1.5	31.20	1.65	3.00
4274	19.8	21.3	1.5	93.94	6.98	14.88
4275	21.3	22.9	1.6	108.00	7.08	12.80
4276	22.9	24.4	1.5	80.57	4.83	9.95
4277	24.4	25.9	1.5	98.74	5.63	12.29
4278	25.9	27.4	1.5	72.69	4.33	8.66
4279	27.4	29.0	1.6	81.60	4.70	9.19
4280	29.0	30.5	1.5	94.63	5.46	11.48
4281	30.5	32.0	1.5	42.51	3.30	5.60
4282	32.0	33.5	1.5	80.57	4.88	8.66
4283	33.5	35.1	1.6	61.37	3.65	7.82
4284	35.1	37.0	1.9	25.37	1.90	4.25
	37.0	50.3	13.3	NOT ASSAYED		
4285	50.3	53.3	3.0	32.23	0.09	1.05
4286	53.3	54.9	1.6	18.17	0.20	0.85
4287	54.9	56.4	1.5	10.97	0.08	0.45
4288	56.4	57.9	1.5	20.23	0.88	1.80
	57.9	76.2	18.3	0.00	0.00	0.00

LATITUDE 2N

DEPARTURE 66W

ELEVATION

DIP AT COLLAR +45°

BEARING 224°

DEPTH 76.2m (250ft)

19.8 - 37.0 = 17.2m (56ft)

Ag 75.30g/t

Pb 4.73%

Zn 9.48%

16.8.76 - 17.8.76

ASSAY NUMBER.	SECTION		CORE LENGTH	ASSAYS		
	FROM (M)	TO (M)		Ag g/t	Pb %	Zn %
	0.0	6.1	6.1	0.00	0.00	0.00
4182	6.1	9.1	3.0	23.31	1.63	2.65
	9.1	27.3	18.2	NOT ASSAYED		
4183	27.3	30.5	3.2	33.26	2.08	2.65
4184	30.5	33.5	3.0	34.29	2.35	4.10
	33.5	38.1	4.6	NOT ASSAYED		
4185	38.1	39.6	1.5	46.29	3.68	3.95
4186	39.6	41.1	1.5	36.34	2.93	3.50
4187	41.1	42.7	1.6	41.49	3.20	4.70
4188	42.7	44.2	1.5	13.71	5.94	7.87
4189	44.2	45.7	1.5	77.83	5.77	6.85
4190	45.7	47.2	1.5	32.23	2.28	3.10
	47.2	51.8	4.6	NOT ASSAYED		
4191	51.8	54.9	3.1	38.40	2.68	4.20
4192	54.9	56.4	1.5	40.46	2.30	5.15
4193	56.4	57.9	1.5	62.40	3.70	7.13
4194	57.9	59.4	1.5	66.51	4.00	7.00
4195	59.4	61.0	1.6	59.31	3.38	6.10
4196	61.0	62.5	1.5	55.54	4.13	5.51
4197	62.5	64.0	1.5	28.46	2.13	2.90
	64.0	68.6	4.6	0.00	0.00	0.00

LATITUDE 3N  
DEPARTURE 18W,  
ELEVATION

DIP AT CORNER -35°  
BEARING 044°  
DEPTH 68.6m (225ft)

30.5 - 33.5 = 3.0m (10ft) Ag 34.29 g/t, Pb 2.35%, Zn 4.10% LOW

38.1 - 47.2 = 9.1m (30ft)

Ag 51.20 g/t

Pb 3.96%

Zn 4.99%

38.1 - 64.0 = 25.9m (85ft)

Ag 40.92 g/t

Pb 2.98%

Zn 4.24%

51.8 - 64.0 = 12.2m (40ft)

Ag 48.69 g/t

Pb 3.37%

Zn 5.27%

18.8.76 - 20.8.76

ASSAY NUMBER	SECTION		CORE LENGTH	ASSAYS		
	FROM (m)	TO (m)		Ag g/t	Pb %	Zn %
4289	0.0	4.6	4.6	9.94	0.73	0.85
4290	4.6	7.6	3.0	19.20	1.83	1.13
4291	7.6	10.7	3.1	7.20	0.58	0.78
4292	10.7	14.0	3.3	16.11	1.13	2.10
4293	14.0	16.8	2.8	30.17	1.68	4.38
4294	16.8	18.3	1.5	20.23	0.73	2.55
4295	18.3	19.8	1.5	35.31	1.78	4.20
4296	19.8	21.3	1.5	48.34	2.90	6.15
4297	21.3	22.9	1.6	44.23	2.60	4.35
4298	22.9	24.4	1.5	97.72	5.11	9.54
4299	24.4	25.9	1.5	58.63	3.70	6.60
	25.9	28.0	2.1	NOT ASSAYED		
4300	28.0	30.5	2.5	31.20	1.93	2.20
4601	30.5	33.0	2.5	90.86	5.49	9.65
	33.0	38.1	5.1	NOT ASSAYED		
4602	38.1	40.0	1.9	36.34	2.30	2.80
	40.0	47.4	7.4	NOT ASSAYED		
4603	47.4	100.0	2.6	14.06	0.73	0.68
	100.0	104.5	4.5	NOT ASSAYED		
4604	104.5	106.4	1.9	30.17	2.05	3.60
4605	106.4	108.2	1.8	106.97	6.57	8.48
4606	108.2	109.7	1.5	34.29	2.23	2.75
4607	109.7	111.3	1.6	40.46	2.90	3.20
4608	111.3	112.8	1.5	48.34	2.65	1.55
	112.8	121.0	8.2	NOT ASSAYED		
4609	121.0	122.0	1.0	70.63	4.80	7.40
	122.0	123.0	1.0	NOT ASSAYED		
4610	123.0	124.0	1.0	50.40	3.78	3.40
	124.0	125.3	1.3	NOT ASSAYED		
4611	125.3	128.0	2.7	64.46	4.30	5.50
4612	128.0	129.5	1.5	47.31	3.18	4.85
4613	129.5	131.6	2.1	79.54	5.20	8.17
4614	131.6	134.1	2.5	25.37	1.45	2.03
4615	134.1	137.2	3.1	9.94	0.63	1.00
4616	137.2	138.7	1.5	43.54	2.28	4.00
4617	138.7	140.2	1.5	82.63	4.93	8.89
4618	140.2	141.7	1.5	19.20	0.38	0.20
	141.7	144.4	2.7	NOT ASSAYED		

CONTINUED ON PAGES 120 & 121

LATITUDE 80° east

DEPARTURE 80W

ELEVATION

DIP AT COLLAR.  $-90^\circ$ 

BEARING.

DEPTH. 182.9 m (600 ft)

18.3 - 25.9 = 7.6 m (25 ft)

Ag 56.58 g/t.

Pb 3.21%

Zn 6.14%

18.3 - 33.0 = 14.7 m (48 ft)

Ag 50.01 g/t

Pb 2.92%

Zn 5.19%

28.0 - 33.0 = 5.0 m (16 ft) Ag 61.03 g/t

Pb 3.71% Zn 5.93%

104.5 - 111.3 = 6.8 m (22 ft)

Ag 52.64 g/t.

Pb 3.40%

Zn 4.52%

121.0 - 131.6 = 10.6 m (35 ft)

Ag 50.29 g/t.

Pb 3.38%

Zn 4.73%

137.2 - 140.2 = 3.0 m (10 ft) Ag 63.1 g/t

Pb 3.61% Zn 6.45%

ASSAY NUMBER	SECTION		CORE LENGTH	ASSAYS		
	FROM	TO		Ag g/t	Pb %	Zn %
4619	144.4	146.3	1.9	22.29	1.28	1.45
4620	146.3	147.8	1.5	17.14	0.53	0.93
4621	147.8	149.4	1.6	19.54	5.71	9.55
4622	149.4	150.9	1.5	30.17	1.60	3.20
4623	150.9	152.4	1.5	28.46	1.58	3.50
4624	152.4	153.9	1.5	30.17	1.33	1.73
4625	153.9	155.4	1.5	36.34	2.03	2.60
	155.4	180.4	25.0	NOT ASSAYED		
4626	180.4	181.6	1.2	59.31	4.50	4.40
	181.6	182.9	<del>1.3</del>	0.00	0.00	0.00

147.8 - 155.4 = 7.6m (25 ft)

Ag 41.44 g/t

Pb 2.49%

Zn 4.18%

LOW

18.6.76 - 21.6.76

ASSAY NUMBER	SECTION		CORE LENGTH	ASSAYS		
	FROM (m)	TO (m)		Ag g/t	Pb %	Zn %
4198	0.0 ✓	3.0 ✓	3.0	41.49 ✓	3.78 ✓	5.00 ✓
4199	3.0 ✓	6.1 ✓	3.1	25.37 ✓	2.30 ✓	1.83 ✓
4200	6.1 ✓	9.1 ✓	3.0	16.11 ✓	1.04 ✓	0.35 ✓
4701	9.1 ✓	12.2 ✓	3.1	13.03 ✓	0.65 ✓	0.35 ✓
4702	12.2 ✓	15.2 ✓	3.0	6.17 ✓	0.40 ✓	0.63 ✓
4703	15.2 ✓	18.3 ✓	3.1	20.23 ✓	1.65 ✓	2.23 ✓
4704 +	18.3 ✓	21.3 ✓	3.0	26.40 ✓	2.23 ✓	2.35 ✓
4705 +	21.3 ✓	22.9 ✓	1.6	20.23 ✓	1.70 ✓	3.80 ✓
4706	22.9 ✓	24.4 ✓	1.5	17.14 ✓	1.20 ✓	1.85 ✓
4707	24.4 ✓	25.9 ✓	1.5	70.63 ✓	5.19 ✓	7.49 ✓
4708	25.9 ✓	27.4 ✓	1.5	30.17 ✓	1.20 ✓	1.10 ✓
4709	27.4 ✓	29.0 ✓	1.6	71.66 ✓	4.60 ✓	5.10 ✓
4710	29.0 ✓	31.5 ✓	2.5	110.06 ✓	6.52 ✓	9.90 ✓
	31.5 ✓	47.5 ✓	16.0	NOT ASSAYED		
4711	47.5 ✓	49.4 ✓	1.9	91.89 ✓	4.88 ✓	10.51 ✓
	49.4 ✓	92.5 ✓	43.1	NOT ASSAYED		
4712	92.5 ✓	94.5 ✓	2.0	23.31 ✓	1.53 ✓	2.78 ✓
	94.5 ✓	137.2 ✓	42.7	NOT ASSAYED		
4713	137.2 ✓	138.7 ✓	1.5	31.20 ✓	2.08 ✓	4.10 ✓
4714	138.7 ✓	140.2 ✓	1.5	143.32 ✓	9.19 ✓	16.37 ✓
4715	140.2 ✓	141.7 ✓	1.5	46.29 ✓	2.60 ✓	6.26 ✓
	141.7 ✓	152.4 ✓	10.7	0.00	0.00	0.00

LATITUDE 3N  
DEPARTURE 80W  
ELEVATION

DIP AT COLLAR -75°  
BEARING 224°  
DEPTH 152.4m (500 ft)

0.0 - 3.0 = 3.0m (10ft) Ag 41.49 g/t; Pb 3.78%; Zn 5.00%

24.4 - 31.5 = 7.1m (23.3ft)  
Ag 76.20 g/t  
Pb 4.68%  
Zn 6.45%

47.5 - 49.4 = 1.9m (6ft) Ag 91.89 g/t; Pb 4.88%; Zn 10.51%

137.2 - 141.7 = 4.5m (14.75ft) Ag 73.70 g/t  
Pb 4.62%  
Zn 8.91%

21.8.76. - 22.8.76.

ASSAY NUMBER	SECTION		CORE LENGTH	ASSAYS		
	From (m)	To (m)		Ag g/t	Pb %	Zn %
4627	0.0	1.5	1.5	86.74	5.58	9.55
4628	1.5	3.0	1.5	113.14	8.25	11.51
4629	3.0	4.6	1.6	143.32	10.42	15.28
4630	4.6	6.1	1.5	185.49	12.23	20.76
4631	6.1	7.6	1.5	23.31	1.40	3.00
4632	7.6	9.1	1.5	35.31	2.25	4.30
4633	9.1	10.7	1.6	37.37	2.58	4.25
4634	10.7	12.2	1.5	39.43	2.53	4.50
4635	12.2	13.7	1.5	51.43	3.10	5.95
4636	13.7	15.2	1.5	89.43	2.28	4.35
4637	15.2	16.8	1.6	132.00	9.19	11.71
4638	16.8	18.3	1.5	94.63	6.17	5.80
4639	18.3	20.4	2.1	60.34	4.05	4.65
	20.4	54.5	34.1	NOT ASSAYED		
4640	54.5	56.4	1.9	71.66	4.89	3.70
4641	56.4	57.9	1.5	47.31	1.93	2.30
4642	57.9	59.4	1.5	70.63	4.80	4.70
4643	59.4	61.0	1.6	124.46	10.44	8.57
4644	61.0	62.5	1.5	192.69	15.89	12.42
4645	62.5	65.1	2.6	111.09	6.62	5.00
	65.1	76.2	11.1	0.00	0.00	0.00

LATITUDE 2N  
DEPARTURE 80W.  
ELEVATION

DIP AT COLLAR 2  
BEARING  
DEPTH. 76.2 m

0.0 - 20.4 = 20.4 m (67 ft)

Ag 79.92 g/t

Pb 5.46 %

Zn 8.15 %

0.0 - 65.1 = 65.1 m (213.6 ft)

Ag 41.79 g/t

Pb 2.89 %

Zn 3.52 %

LOW

54.5 - 65.1 = 10.6 m (35 ft)

Ag 102.84 g/t

Pb 7.28 %

Zn 5.93 %

23.8.76 - 24.8.76

ASSAY NUMBER	SECTION		CORE LENGTH	ASSAYS		
	FROM	TO		Ag g/t	Pb %	Zn %
4743	0.0 18.7	18.7 21.3	18.7 2.6	6.00 17.14	0.00 1.33	0.00 2.58
4744	21.3	24.4	3.1	33.26	2.88	3.30
4745	24.4	27.4	3.0	9.94	0.78	0.90
4746	27.4	30.5	3.1	5.14	0.33	0.43
	30.5	33.5	3.0	NOT ASSAYED		
4747	33.5	36.6	3.1	25.37	1.68	2.68
4748	36.6	38.1	1.5	35.31	2.43	4.00
4749	38.1	39.6	1.5	42.51	2.48	4.95
4750	39.6	41.1	1.5	45.26	2.45	5.40
4751	41.1	42.7	1.6	28.46	1.65	3.15
4752	42.7	44.2	1.5	47.31	3.13	4.00
4753	44.2	46.6	2.4	99.77	6.74	9.04
	46.6	61.0	14.4	0.00	0.00	0.00

LATITUDE

DEPARTURE

ELEVATION

DIP AT COLLAR -17° P

BEARING 224° P

DEPTH 61m (200ft)

21.3 - 24.4 = 3.1m (10ft) Ag 33.26g/t. Pb 2.88%. Zn 3.30% **LOW**

36.6 - 46.6 = 10.0m (33ft)

Ag 54.06g/t

Pb 3.46%

Zn 5.43%

21.8.76      22.8.76

ASSAY NUMBER	SECTION		CORE LENGTH	ASSAYS		
	FROM (m)	TO (m)		Ag g/t	Pb %	Zn %
4716	0.0 ✓	1.5 ✓	1.5	63.43 ✓	4.42 ✓	9.69 ✓
4717	1.5 ✓	3.0 ✓	1.5	78.86 ✓	5.18 ✓	9.47 ✓
4718	3.0 ✓	4.6 ✓	1.6	44.23 ✓	2.88 ✓	5.78 ✓
4719	4.6 ✓	6.1 ✓	1.5	94.63 ✓	5.82 ✓	9.22 ✓
4720	6.1 ✓	7.6 ✓	1.5	50.40 ✓	3.60 ✓	8.50 ✓
4721	7.6 ✓	9.1 ✓	1.5	80.57 ✓	6.07 ✓	12.53 ✓
4722	9.1 ✓	10.7 ✓	1.6	80.57 ✓	6.19 ✓	12.47 ✓
4723	10.7 ✓	12.2 ✓	1.5	59.31 ✓	4.30 ✓	7.37 ✓
4724	12.2 ✓	13.7 ✓	1.5	64.46 ✓	4.55 ✓	8.95 ✓
4725	13.7 ✓	15.2 ✓	1.5	55.54 ✓	3.50 ✓	8.10 ✓
4726	15.2 ✓	16.8 ✓	1.6	33.26 ✓	2.13 ✓	3.83 ✓
4727	16.8 ✓	18.3 ✓	1.5	22.29 ✓	1.40 ✓	1.90 ✓
4728	18.3 ✓	19.8 ✓	1.5	30.17 ✓	1.68 ✓	3.75 ✓
4729	19.8 ✓	21.3 ✓	1.5	35.31 ✓	2.15 ✓	4.55 ✓
4730	21.3 ✓	22.9 ✓	1.6	48.34 ✓	3.38 ✓	7.26 ✓
4731	22.9 ✓	24.4 ✓	1.5	24.34 ✓	1.18 ✓	1.40 ✓
4732	24.4 ✓	25.9 ✓	1.5	15.09 ✓	0.53 ✓	0.93 ✓
4733	25.9 ✓	27.4 ✓	1.5	35.31 ✓	1.85 ✓	2.70 ✓
4734	27.4 ✓	29.0 ✓	1.6	60.34 ✓	4.40 ✓	8.25 ✓
4735	29.0 ✓	30.5 ✓	1.5	33.26 ✓	2.15 ✓	2.70 ✓
4736	30.5 ✓	32.0 ✓	1.5	124.46 ✓	8.41 ✓	11.16 ✓
4737	32.0 ✓	33.5 ✓	1.5	104.92 ✓	7.06 ✓	9.10 ✓
4738	33.5 ✓	35.1 ✓	1.6	195.17 ✓	12.69 ✓	22.43 ✓
4739	35.1 ✓	36.6 ✓	1.5	98.74 ✓	6.47 ✓	11.46 ✓
4740	36.6 ✓	38.1 ✓	1.5	86.74 ✓	5.27 ✓	6.58 ✓
4741	38.1 ✓	39.6 ✓	1.5	16.11 ✓	0.95 ✓	0.80 ✓
4742	39.6 ✓	42.2 ✓	2.6	90.86 ✓	5.42 ✓	7.19 ✓
	42.2 ✓	61.0 ✓	18.8	0.00	0.00	0.00

LATITUDE  
DEPARTURE  
ELEVATION

DIP AT COLLAR -17°  
BEARING 224°  
DEPTH 61 m (200 ft)

0.0 - 42.2 = 42.2 m (138.5 ft)

Ag 64.79 g/t  
Pb 4.26 %  
Zn 7.37 %

23. 8. 76 - 24. 8. 76

ASSAY NUMBER	SECTION		CORE LENGTH	ASSAYS		
	FROM (m)	TO (m)		Ag g/t	Pb %	Zn %
4646	0.0	3.0	3.0	44.23	3.13	6.01
4647	3.0	4.6	1.6	46.29	3.35	4.55
4648	4.6	6.1	1.5	70.63	4.45	8.14
4649	6.1	7.6	1.5	136.12	9.34	14.83
4650	7.6	9.1	1.5	34.29	2.03	3.70
4651	9.1	10.7	1.6	22.29	1.30	2.53
4652	10.7	12.2	1.5	39.43	2.50	5.10
4653	12.2	13.7	1.5	55.40	3.80	7.04
4654	13.7	15.2	1.5	68.57	4.65	9.90
4655	15.2	16.8	1.6	30.17	1.63	3.83
4656	16.8	18.3	1.5	52.46	3.68	6.51
4657	18.3	19.8	1.5	12.00	0.63	1.05
4658	19.8	21.3	1.5	78.86	4.80	8.74
4659	21.3	22.9	1.6	68.57	3.88	6.34
4660	22.9	24.4	1.5	27.43	1.55	2.03
4661	24.4	26.8	2.4	69.60	4.05	6.06
	26.8	61.0	34.2	0.00	0.00	0.00

LATITUDE  
DEPARTURE  
ELEVATION

DIP AT COLLAR. + 83°  
BEARING. 224°  
DEPTH. 61 m (200 ft)

0.0 - 26.8 = 26.8 m (88 ft)

Ag 53.37 g/t.

Pb 3.42%

Zn 5.99%

E.C.J.

24.8.76 - 25.8.76

ASSAY NUMBER	SECTION		CORE LENGTH	ASSAYS		
	FROM (m)	TO (m)		Ag g/t	Pb %	Zn %
	0.0	1.5	<del>1.5</del> 3.1	8.00	0.00	0.00
4754	1.5	4.6	3.1	5.14	0.10	0.30
4755	4.6	7.6	3.0	8.23	0.20	1.00
4756	7.6	9.1	1.5	30.17	1.78	1.95
4757	9.1	10.7	1.6	17.14	1.23	2.30
4758	10.7	12.2	1.5	18.17	1.30	2.25
4759	12.2	13.7	1.5	12.00	0.55	1.35
4760	13.7	15.2	1.5	10.97	0.43	0.58
4761	15.2	16.8	1.6	4.11	0.08	0.98
4762	16.8	19.8	3.0	8.91	0.18	0.60
4763	19.8	22.9	3.1	4.11	0.05	0.98
4764	22.9	25.9	3.0	8.23	0.18	0.73
4765	25.9	29.0	3.1	8.91	0.48	0.73
4766	29.0	32.0	3.0	9.94	0.05	0.78
4767	32.0	35.1	3.1	12.00	0.10	1.13
4768	35.1	38.1	3.0	13.03	0.13	2.08
4769	38.1	41.1	3.0	14.06	0.20	1.65
4770	41.1	44.2	3.1	22.29	0.63	1.88
4771	44.2	47.2	3.0	15.09	0.20	1.33
4772	47.2	50.3	3.1	22.29	1.08	1.53
4773	50.3	53.0	2.7	38.40	1.30	3.65
	53.0	61.0	8.0	0.00	0.00	0.00

LOW VALUES

LATITUDE 2N  
DEPARTURE 66W  
ELEVATION

DIP AT COLLAR -56°  
BEARING 224°  
DEPTH 61m (200ft)

25.8.76 - 26.8.76

ASSAY NUMBER	SECTION		CORE LENGTH	ASSAYS		
	FROM (M)	TO (M)		Ag g/t	Pb %	Zn %
4662	0.0 ✓	4.6 ✓	4.6	32.23 ✓	2.68 ✓	2.59 ✓
4663	4.6 ✓	6.1 ✓	1.5	22.29 ✓	1.80 ✓	2.83 ✓
4664	6.1 ✓	7.6 ✓	1.5	16.11 ✓	1.30 ✓	2.00 ✓
4665	7.6 ✓	9.1 ✓	1.5	10.97 ✓	0.98 ✓	1.68 ✓
	9.1 ✓	47.2 ✓	38.1	NOT ASSAYED		
4666	47.2 ✓	50.3 ✓	3.1	19.20 ✓	1.28 ✓	1.85 ✓
4667	50.3 ✓	51.8 ✓	1.5	45.26 ✓	3.90 ✓	3.10 ✓
4668	51.8 ✓	53.3 ✓	1.5	14.06 ✓	0.18 ✓	0.45 ✓
4669	53.3 ✓	54.9 ✓	1.5	72.69 ✓	4.75 ✓	6.33 ✓
4670	54.9 ✓	56.4 ✓	1.5	80.57 ✓	6.15 ✓	9.89 ✓
4671	56.4 ✓	57.9 ✓	1.5	88.80 ✓	5.00 ✓	7.28 ✓
4672	57.9 ✓	59.4 ✓	1.5	98.74 ✓	6.25 ✓	9.99 ✓
4673	59.4 ✓	61.0 ✓	1.6	80.57 ✓	4.25 ✓	7.79 ✓
4674	61.0 ✓	62.5 ✓	1.5	84.69 ✓	4.28 ✓	7.39 ✓
4675	62.5 ✓	64.0 ✓	1.5	92.92 ✓	5.00 ✓	7.46 ✓
4676	64.0 ✓	65.5 ✓	1.5	38.40 ✓	1.65 ✓	2.88 ✓
	65.5 ✓	76.2 ✓	10.7	0.00	0.00	0.00

LATITUDE  
DEPARTURE  
ELEVATION

DIP AT COLLAR -90°  
BEARING  
DEPTH 76.2m (250ft)

$50.3 - 64.0 = 13.7m (45ft)$

Ag 72.66 g/t

Pb 4.38%

Zn 6.53%

25.8.76 - 27.8.76

ASSAY NUMBER	SECTION		CORE LENGTH	ASSAYS		
	FROM (M)	TO (M)		Ag g/t	Pb %	Zn %
4774	0.0	4.6	4.6	10.97	0.53	1.80
4775	4.6	6.1	1.5	16.11	0.83	1.70
4776	6.1	7.6	1.5	30.17	2.25	2.45
4777	7.6	9.1	1.5	22.29	1.30	1.08
4778	9.1	10.7	1.6	8.91	0.45	1.18
4779	10.7	12.2	1.5	4.11	0.08	0.40
4780	12.2	13.7	1.5	7.20	0.13	1.95
4781	13.7	15.2	1.5	7.20	0.15	1.00
4782	15.2	16.8	1.6	10.97	0.13	0.63
4783	16.8	18.3	1.5	22.29	0.65	1.10
4784	18.3	22.9	3.6	6.17	0.10	0.18
4785	22.9	24.4	1.5	6.17	0.13	0.13
4786	24.4	27.4	3.0	5.14	0.10	1.35
4787	27.4	30.5	3.1	3.09	0.02	0.18
4788	30.5	33.5	3.0	4.11	0.05	0.63
4789	33.5	36.6	3.1	5.14	0.02	0.33
4790	36.6	39.6	3.0	3.09	0.02	0.20
4791	39.6	42.7	3.1	2.06	0.05	0.23
4792	42.7	44.2	1.5	20.23	1.15	2.80
4793	44.2	46.0	1.8	40.46	2.50	3.15
-	46.0	121.3	75.3	NOT ASSAYED		
4794	121.3	123.4	2.1	108.00	6.00	9.39
4795	123.4	125.0	1.6	100.80	6.30	1.78
4796	125.0	127.0	2.0	35.31	2.28	2.45
	127.0	132.6	5.6	0.00	0.00	0.00

LATITUDE 2N  
 DEPARTURE 66W  
 ELEVATION

DIP AT COLLAR. -90°  
 BEARING.  
 DEPTH. 132.6m (435 ft)

121.3 - 127.0 = 5.7m (18.7ft) Ag. 80.47 g/t  
 Pb 4.78%  
 Zn 6.50%

E.C.J.

DPH U 158 ✓

26. 8. 76 - 27. 8. 76

ASSAY NUMBER	SECTION		CORE LENGTH	ASSAYS		
	FROM (M)	TO (M)		Ag g/t	Pb %	Zn %
4677	0.0 ✓	3.0 ✓	3.0	46.29 ✓	3.03 ✓	5.95 ✓
4678	3.0 ✓	4.6 ✓	1.6	48.34 ✓	2.98 ✓	6.03 ✓
4679	4.6 ✓	6.1 ✓	1.5	124.12 ✓	7.68 ✓	10.09 ✓
4680	6.1 ✓	7.6 ✓	1.5	138.17 ✓	9.45 ✓	16.21 ✓
4681	7.6 ✓	9.1 ✓	1.5	78.86 ✓	5.30 ✓	11.85 ✓
4682	9.1 ✓	10.7 ✓	1.6	34.29 ✓	1.93 ✓	3.40 ✓
4683	10.7 ✓	12.2 ✓	1.5	60.34 ✓	3.95 ✓	6.71 ✓
4684	12.2 ✓	13.7 ✓	1.5	58.63 ✓	3.93 ✓	9.69 ✓
4685	13.7 ✓	16.8 ✓	3.1	25.37 ✓	1.53 ✓	2.60 ✓
	16.8 ✓	39.5 ✓	22.7	NOT ASSAYED		
4686	39.5 ✓	42.7 ✓	3.2	25.37 ✓	2.00 ✓	1.78 ✓
	42.7 ✓	45.5 ✓	2.8	NOT ASSAYED		
4687	45.5 ✓	47.2 ✓	1.7	95.66 ✓	6.30 ✓	6.45 ✓
	47.2 ✓	68.6 ✓	21.4	NOT ASSAYED		
4688	68.6 ✓	70.2 ✓	1.6	10.97 ✓	0.45 ✓	0.58 ✓
	70.2 ✓	<del>74.0</del> 74.3	<del>3.8</del> 4.1	0.00	0.00	0.00

LATITUDE 3N,  
DEPARTURE 82W,  
ELEVATION

DIP AT COLLAR +45°  
BEARING 224°  
DEPTH 74.3 ~~74.3~~ m (244 ~~244~~ ft)

0.0 - 13.7 = 13.7m (45 ft)  
Ag 69.81 g/t.  
Pb 4.56%  
Zn 8.38%

45.5 - 47.2 = 1.7m (5.6 ft) Ag 95.66 g/t.  
Pb 6.30% Zn 6.45%

27.8.1976 - 28.8.76

ASSAY NUMBER

SECTION FROM (m) / 10m

COKE LENGTH 1977

ASSAYS Hg g/t Pb % Zn %

0.0 19.7 19.7 8.91 0.20 0.00

21.3 22.9 25.9 9.94 0.05 1.05

22.9 25.9 29.2 15.09 0.18 3.0

25.9 29.2 30.5 25.37 1.45 3.1

29.0 30.5 32.0 28.63 6.76 1.5

30.5 32.0 32.0 29.94 5.81 1.5

32.0 32.0 32.0 32.0 11.17 19.8

51.8 53.3 54.9 50.40 4.20 1.5

53.3 54.9 56.4 46.51 5.00 1.6

54.9 56.4 57.9 22.29 1.05 1.5

56.4 57.9 59.4 49.37 2.75 1.5

57.9 59.4 59.4 22.29 1.28 1.5

59.4 61.0 61.0 58.63 3.88 1.6

61.0 62.5 62.5 26.40 1.63 1.5

62.5 64.0 64.0 25.37 1.55 1.5

64.0 65.5 65.5 10.97 0.50 1.5

65.5 67.1 67.1 26.40 1.50 1.6

67.1 68.6 68.6 48.34 2.53 1.5

68.6 70.1 70.1 21.26 1.05 1.5

70.1 71.6 71.6 20.23 1.20 1.5

71.6 73.2 73.2 30.17 5.84 1.6

73.2 74.7 74.7 33.26 2.30 1.5

74.7 76.2 76.2 47.31 3.23 1.5

4846

4847

4848

4849

4850

4851

4852

4853

4854

4855

4856

4857

4858

4859

4860

4861

4862

4863

4864

4865

4866

4867

LATITUDE 2N

DEPARTURE 04m

ELEVATION

DIP AT CORNER + 69°

BEARING 044°

LENGTH 76.8m (250ft)

51.8 - 61.0 = 9.2m (30ft)

Hg 50.40 g/t

Pb 3.06%

Zn 4.02%

29.0 - 32.0 = 3.0m (10ft) Hg 88.29 g/t

Pb 6.29%

Zn 10.47%

71.6 - 76.2 - 4.6m (15ft)

Hg 36.77 g/t Pb 3.83%

Zn 5.05%

27.8.76 - 28.8.76

ASSAY NUMBER	SECTION		CORE LENGTH	ASSAYS		
	From (m)	To (m)		Ag g/t	Pb %	Zn %
4689	0.0 ✓	4.6 ✓	4.6	28.46 ✓	2.43 ✓	2.55 ✓
4690	4.6 ✓	7.0 ✓	2.4	32.23 ✓	2.73 ✓	4.75 ✓
4691	7.0 ✓	10.0 ✓	3.0	18.17 ✓	1.13 ✓	2.45 ✓
4692	10.0 ✓	12.2 ✓	2.2	52.46 ✓	3.30 ✓	6.18 ✓
4693	12.2 ✓	13.7 ✓	1.5	66.51 ✓	4.95 ✓	6.78 ✓
4694	13.7 ✓	15.2 ✓	1.5	75.77 ✓	5.20 ✓	7.98 ✓
4695	15.2 ✓	16.8 ✓	1.6	75.77 ✓	5.48 ✓	8.44 ✓
4696	16.8 ✓	18.3 ✓	1.5	118.97 ✓	7.18 ✓	8.73 ✓
4697	18.3 ✓	19.6 ✓	1.5	110.06 ✓	7.42 ✓	13.21 ✓
	19.6	22.9	3.3	NOT ASSAYED		
4698	22.9 ✓	24.4 ✓	1.5	34.29 ✓	2.00 ✓	4.45 ✓
4699	24.4 ✓	25.9 ✓	1.5	38.40 ✓	2.13 ✓	4.30 ✓
4700	25.9 ✓	27.4 ✓	1.5	75.77 ✓	4.88 ✓	7.59 ✓
4798	27.4 ✓	29.0 ✓	1.6	37.37 ✓	2.30 ✓	4.45 ✓
4799	29.0 ✓	30.5 ✓	1.5	67.54 ✓	4.08 ✓	6.08 ✓
4800	30.5 ✓	32.0 ✓	1.5	75.77 ✓	5.00 ✓	8.25 ✓
4801	32.0 ✓	33.5 ✓	1.5	40.46 ✓	2.28 ✓	4.88 ✓
	33.5	36.0	2.5	NOT ASSAYED		
4802	36.0 ✓	37.1 ✓	1.1	84.69 ✓	5.34 ✓	7.08 ✓
	37.1	38.4	1.3	NOT ASSAYED		
4803	38.4 ✓	40.2 ✓	1.8	49.03 ✓	3.30 ✓	3.95 ✓
4804	40.2 ✓	42.7 ✓	2.5	145.03 ✓	8.76 ✓	14.98 ✓
4805	42.7 ✓	44.4 ✓	1.7	156.34 ✓	9.16 ✓	16.02 ✓
	44.4	45.3	0.9	NOT ASSAYED		
4806	45.3 ✓	47.2 ✓	1.9	55.54 ✓	3.00 ✓	2.85 ✓
4807	47.2 ✓	49.8 ✓	2.6	30.17 ✓	1.60 ✓	2.55 ✓
4808	49.8 ✓	51.8 ✓	2.0	120.00 ✓	7.24 ✓	12.00 ✓
4809	51.8 ✓	54.9 ✓	3.1	100.80 ✓	5.45 ✓	10.35 ✓
4810	54.9 ✓	57.9 ✓	3.0	94.63 ✓	5.65 ✓	10.09 ✓
4811	57.9 ✓	59.4 ✓	1.5	80.57 ✓	5.80 ✓	9.85 ✓
4812	59.4 ✓	61.0 ✓	1.6	101.83 ✓	5.75 ✓	9.38 ✓
4813	61.0 ✓	62.5 ✓	1.5	129.94 ✓	7.00 ✓	10.25 ✓
4814	62.5 ✓	65.0 ✓	2.5	115.89 ✓	6.60 ✓	9.70 ✓
	65.0	67.1	2.1	NOT ASSAYED		
4815	67.1 ✓	68.6 ✓	1.5	69.60 ✓	3.88 ✓	6.23 ✓
	68.6	73.2	4.6	0.00	0.00	0.00

LATITUDE 3N  
 DEPARTURE 82W.  
 ELEVATION

DIP AT COLLAR  $-15^{\circ}$   
 BEARING  $224^{\circ}$   
 DEPTH 73.2m (240ft).

$$4.6 - 19.6 = 15.0m (49ft)$$

Ag 61.7 g/t.  
 Pb 4.21%  
 Zn 6.76%

$$4.6 - 33.5 = 28.9m (95ft)$$

Ag 59.04 g/t  
 Pb 3.67%  
 Zn 5.60%

$$22.9 - 33.5 = 10.6m (35ft)$$

Ag 73.66 g/t  
 Pb 3.23%  
 Zn 5.70%

$$4.6 - 37.1 = 32.5m (106.6ft)$$

Ag 55.37 g/t.  
 Pb 3.18%  
 Zn 5.22%

$$4.6 - 44.4 = 39.8m (130.5ft)$$

$38.4 - 44.4 = 6.0m (19.7ft)$   
 Ag 119.43 g/t Pb 7.24%  
 Zn 11.97%

Ag 63.22 g/t.  
 Pb 3.68%  
 Zn 6.07%

$$45.3 - 65.0 = 19.7m (64.6ft)$$

Ag 90.80 g/t.  
 Pb 5.24%  
 Zn 8.52%

$$4.6 - 65.0 = 60.4m (198ft)$$

Ag 71.27 g/t  
 Pb 4.14%  
 Zn 6.78%

$4.6 - 68.6 = 64m (210ft)$  Ag 68.89 g/t Pb 4.03%  
 Zn 5.22%

28.8.76 - 29.8.76

ASSAY SECTION COKE ASSAYS

ASSAY NUMBER	Section	COKE	From (m) / 10 (m) LENGTH	Ag %	Pb %	Zn %
4817	4.6	3.0	4.6	8.91	0.18	0.80
4818	7.6	1.5	7.6	7.80	0.13	0.58
4819	9.1	1.6	12.00	12.00	0.55	1.10
4820	10.7	1.5	20.23	1.18	2.73	
4821	13.7	1.5	52.46	3.48		
4822	15.2	1.5	28.46	1.75		
4823	16.8	1.6	95.66	7.86	9.22	
4824	18.3	1.5	44.23	3.18	3.60	
4825	19.8	1.5	30.17	1.70	0.78	
4826	21.3	1.5	54.51	3.90	2.60	
4827	22.9	1.6	103.89	7.66	10.30	
4828	24.4	1.5	158.40	8.66	17.08	
4829	25.9	1.5	100.80	6.61	9.80	
4830	27.4	1.5	108.00	6.10	10.70	
4831	29.0	1.6	140.23	9.20	10.60	
4832	30.5	1.5	91.89	6.50	8.89	
4833	32.0	1.5	88.80	6.28	8.40	
4834	33.5	1.5	96.69	7.20	9.65	
4835	35.1	1.6	38.40	2.90	3.35	
4836	36.6	1.5	42.51	3.10	4.15	
4837	38.1	1.5	46.29	3.48	4.75	
4838	40.2	2.1	21.26	2.05	2.90	
4839	42.2	2.0	34.29	3.25	4.65	
4840	44.2	2.0	8.23	0.23	0.30	
4841	46.2	2.0	9.94	0.08	0.48	
4842	48.2	2.0	13.03	0.18	0.70	
4843	50.2	2.0	20.23	0.28	1.00	
4844	52.2	3.1	70.13	5.15	4.80	
4845	54.4	1.1	54.4	1.1		
NOT ASSAYED						
54.4	56.1	1.7	42.69	6.01	8.40	
56.1	59.4	3.3	0.00	0.00	0.00	

LATITUDE 2N  
DEPARTURE 66W.  
ELEVATION

DIP AT COLLAR -  $33^{\circ}$   
BEARING  $224^{\circ}$   
DEPTH. 59.4 m (195 ft)

$$12.2 - 56.1 = 43.9 \text{ m (144 ft)}$$

Ag 61.5 g/t.

Pb 4.03 %

Zn 5.22 %

30. 8. 76 - 31. 8. 76

ASSAY NUMBER	SECTION		CORE LENGTH	ASSAYS		
	FROM (M)	TO (M)		Ag g/t	Pb%	Zn%
4868	0.0	10.1	10.1	8.00	0.00	0.00
	10.1	12.2	2.1	27.43	1.90	0.43
4869	12.2	15.2	3.0	12.00	0.63	0.33
4870	15.2	18.3	3.1	24.34	1.55	0.98
4871	18.3	21.3	3.0	9.94	0.78	1.25
4872	21.3	24.4	3.1	16.11	1.20	2.05
4873	24.4	25.9	1.5	10.97	0.60	1.55
4874	25.9	27.6	1.7	67.54	4.18	5.93
	27.6	34.6	7.0	NOT ASSAYED		
4875	34.6	35.5	0.9	85.72	4.48	8.93
	35.5	49.2	13.7	NOT ASSAYED		
4876	49.2	50.3	1.1	134.06	7.45	12.72
4877	50.3	51.8	1.5	139.20	8.25	18.54
4878	51.8	53.3	1.5	68.57	4.18	8.68
4879	53.3	54.9	1.6	186.52	7.45	11.31
	54.9	100.4	45.5	NOT ASSAYED		
4880	100.4	102.1	1.7	21.26	1.55	2.18
4881	102.1	103.6	1.5	28.46	2.00	2.75
4882	103.6	105.2	1.6	15.09	1.05	1.28
4883	105.2	106.7	1.5	28.46	2.00	2.70
4884	106.7	108.2	1.5	15.09	0.93	1.08
4885	108.2	109.7	1.5	5.14	0.13	0.13
4886	109.7	111.3	1.6	10.97	0.98	1.03
4887	111.3	112.8	1.5	23.31	1.68	2.50
	112.8	142.1	29.3	NOT ASSAYED		
4888	142.1	143.6	1.5	44.23	2.48	4.85
4889	143.6	145.1	1.5	16.11	1.00	2.35
4890	145.1	146.6	1.5	75.77	5.00	7.06
	146.6	153.9	7.3	0.00	0.00	0.00

LATITUDE 3N  
DEPARTURE 82W  
ELEVATION

DIP AT COLLAR  $-65^{\circ}$   
BEARING  $224^{\circ}$   
DEPTH 153.9 m (505 ft)

$25.9 - 27.6 = 1.7 \text{ m (5.6 ft)}$  Ag. 67.54 g/t. Pb 4.18%. Zn 5.93%.

$34.6 - 35.5 = 0.9 \text{ m (3 ft)}$  Ag. 85.72 g/t. Pb 4.48%. Zn 8.43%.

$49.2 - 54.9 = 5.7 \text{ m (18 ft)}$

Ag 132.9 g/t

Pb 6.8%

Zn 12.79%

$142.1 - 146.6 = 4.5 \text{ m (14.8 ft)}$

Ag. 45.37 g/t Pb 2.83%

Zn 4.75%

D. D H U 162 A.

LATITUDE 3N  
DEPARTURE 82W  
ELEVATION

DIP AT COLLAR  
BEARING  $224^{\circ}$   
DEPTH 47.2 m (155 ft)

NO INTERSECTION.

(E.C.)

31.8.76 - 1.9.76

ASSAY NUMBER	SECTION		CORE LENGTH	ASSAYS		
	FROM (m)	TO (m)		Ag g/t	Pb%	Zn%
001 B	0.0 ✓	3.0 ✓	3.0	6.17 ✓	0.10 ✓	1.68 ✓
002 B	3.0 ✓	6.1 ✓	3.1	13.03 ✓	0.33 ✓	1.13 ✓
003 B	6.1 ✓	8.0 ✓	1.9	35.31 ✓	2.15 ✓	3.75 ✓
	8.0 ✓	60.5 ✓	52.5	NOT ASSAYED		
004 B	60.5 ✓	63.1 ✓	2.6	77.83 ✓	4.75 ✓	8.64 ✓
	63.1 ✓	86.9 ✓	23.8	NOT ASSAYED		
005 B	86.9 ✓	90.1 ✓	3.2	33.24 ✓	2.50 ✓	1.90 ✓
006 B	90.1 ✓	93.1 ✓	3.0	39.43 ✓	3.95 ✓	2.40 ✓
007 B	93.1 ✓	96.0 ✓	2.9	24.34 ✓	1.73 ✓	1.45 ✓
	96.0 ✓	112.1 ✓	16.1	0.00	0.00	0.00

LATITUDE 25°  
 DEPARTURE 64W  
 ELEVATION  
 DIP AT COLLAR  
 BEARING 224°  
 DEPTH 112.1 m (368 ft)

6.1 - 8.0 = 1.9 m (6.2 ft) Ag 35.31 g/t Pb 2.15% Zn 3.75% LOW

60.5 - 63.1 = 2.6 m (8.5 ft) Ag 77.83 g/t Pb 4.75% Zn 8.64%

90.1 - 93.1 = 3.0 m (10.0 ft) Ag 39.43 g/t Pb 3.95% Zn 2.40% LOW

2.9.76 - 2.9.76

ASSAY NUMBER	SECTION		C.R.E. LENGTH	ASSAYS		
	FROM (M)	TO (M)		Ag g/t	Pb %	Zn %
026 B	0.0 ✓	3.0 ✓	3.0	61.37 ✓	4.45 ✓	5.83 ✓
027 B	3.0 ✓	4.6 ✓	1.6	89.83 ✓	5.39 ✓	7.17 ✓
028 B	4.6 ✓	6.1 ✓	1.5	111.09 ✓	7.13 ✓	12.01 ✓
029 B	6.1 ✓	7.6 ✓	1.5	60.34 ✓	3.83 ✓	7.06 ✓
030 B	7.6 ✓	9.1 ✓	1.5	27.43 ✓	1.48 ✓	2.98 ✓
031 B	9.1 ✓	10.7 ✓	1.6	71.66 ✓	4.00 ✓	4.65 ✓
032 B	10.7 ✓	12.2 ✓	1.5	142.29 ✓	6.50 ✓	13.82 ✓
	12.2 ✓	41.1 ✓	28.9	NOT ASSAYED		
033 B	41.1 ✓	42.7 ✓	1.6	15.09 ✓	1.13 ✓	0.93 ✓
034 B	42.7 ✓	44.2 ✓	1.5	15.77 ✓	5.25 ✓	4.60 ✓
035 B	44.2 ✓	45.7 ✓	1.5	45.26 ✓	8.00 ✓	1.38 ✓
	45.7 ✓	50.0 ✓	4.3	0.00	0.00	0.00

LATITUDE 3N  
 DEPARTURE 82W  
 ELEVATION

DIP AT COLLAR  
 BEARING  
 DEPTH 50m (164 ft)

0.0 - 12.2 = 12.2m (40ft)

Ag 78.21 g/t  
 Pb 4.65 %  
 Zn 7.36 %

42.7 - 45.7 = 3.0m (10ft) Ag 60.52 g/t  
 Pb 4.13 % Zn 2.99 %

(E.C.J.)

31.8.76 - 1.9.76

ASSAY NUMBER	SECTION		CORE LENGTH	ASSAYS		
	FROM (M)	TO (M)		Ag g/t	Pb %	Zn %
008 B	0.0 ✓	3.0 ✓	3.0	31.20 ✓	2.85 ✓	3.59 ✓
009 B	3.0 ✓	6.1 ✓	3.0	9.94 ✓	0.75 ✓	1.15 ✓
010 B	6.1 ✓	7.6 ✓	1.5	7.20 ✓	0.10 ✓	0.70 ✓
011 B	7.6 ✓	9.5 ✓	1.9	25.37 ✓	0.85 ✓	1.55 ✓
	9.5 ✓	18.2 ✓	8.7	NOT ASSAYED.		
012 B	18.2 ✓	21.3 ✓	3.1	23.31 ✓	0.73 ✓	0.78 ✓
013 B	21.3 ✓	24.4 ✓	3.1	12.00 ✓	0.13 ✓	1.13 ✓
014 B	24.4 ✓	27.4 ✓	3.0	25.37 ✓	1.15 ✓	1.30 ✓
015 B	27.4 ✓	30.5 ✓	3.1	13.03 ✓	0.08 ✓	0.70 ✓
016 B	30.5 ✓	33.5 ✓	3.0	10.97 ✓	0.03 ✓	0.48 ✓
017 B	33.5 ✓	36.6 ✓	3.1	10.97 ✓	0.25 ✓	0.75 ✓
018 B	36.6 ✓	38.1 ✓	1.5	58.40 ✓	2.23 ✓	2.95 ✓
019 B	38.1 ✓	39.6 ✓	1.5	32.23 ✓	1.83 ✓	2.23 ✓
020 B	39.6 ✓	41.6 ✓	2.0	24.34 ✓	1.10 ✓	0.98 ✓
	41.6 ✓	53.3 ✓	11.7	0.00	0.00	0.00

LOW.

LATITUDE 2N  
 DEPARTURE 64W.  
 ELEVATION.

DIP AT COLLAR -41°  
 BEARING 224°  
 DEPTH. 53.3m (175ft)

3.9.76 - 5.9.76

ASSAY NUMBER	SECTION		CORE LENGTH	ASSAYS		
	FROM (M)	TO (M)		Ag %	Pb %	Zn %
058 B	0.0 ✓	1.8 ✓	1.8	52.46 ✓	2.23 ✓	4.48 ✓
059 B	1.8 ✓	3.0 ✓	1.2	66.51 ✓	3.38 ✓	6.88 ✓
060 B	3.0 ✓	4.6 ✓	1.6	15.09 ✓	0.83 ✓	1.13 ✓
	4.6 ✓	35.1 ✓	30.5	NOT ASSAYED		
061 B	35.1 ✓	36.6 ✓	1.5	67.54 ✓	4.45 ✓	7.34 ✓
062 B	36.6 ✓	38.1 ✓	1.5	34.29 ✓	2.15 ✓	1.90 ✓
063 B	38.1 ✓	40.2 ✓	2.1	25.37 ✓	1.73 ✓	2.18 ✓
	40.2 ✓	47.5 ✓	7.3	NOT ASSAYED		
064 B	47.5 ✓	49.0 ✓	1.5	20.23 ✓	1.20 ✓	1.35 ✓
	49.0 ✓	51.6 ✓	2.6	NOT ASSAYED		
065 B	51.6 ✓	53.3 ✓	1.7	17.14 ✓	0.95 ✓	1.70 ✓
066 B	53.3 ✓	54.9 ✓	1.6	14.06 ✓	0.88 ✓	2.00 ✓
	54.9 ✓	112.8 ✓	57.9	NOT ASSAYED		
067 B	112.8 ✓	114.0 ✓	1.2	10.97 ✓	0.70 ✓	0.90 ✓
068 B	114.0 ✓	115.8 ✓	1.8	59.31 ✓	3.18 ✓	4.75 ✓
069 B	115.8 ✓	117.3 ✓	1.5	53.49 ✓	3.53 ✓	4.40 ✓
070 B	117.3 ✓	118.9 ✓	1.6	49.03 ✓	3.18 ✓	3.85 ✓
071 B	118.9 ✓	120.4 ✓	1.5	50.40 ✓	2.78 ✓	4.10 ✓
	120.4 ✓	122.1 ✓	1.7	NOT ASSAYED		
072 B	122.1 ✓	123.6 ✓	1.5	15.09 ✓	0.98 ✓	1.68 ✓
	123.6 ✓	131.1 ✓	7.5	NOT ASSAYED		
073 B	131.1 ✓	132.6 ✓	1.5	9.94 ✓	0.58 ✓	0.55 ✓
074 B	132.6 ✓	134.1 ✓	1.5	22.29 ✓	1.45 ✓	2.48 ✓
075 B	134.1 ✓	135.6 ✓	1.5	15.09 ✓	0.80 ✓	1.45 ✓
	135.6 ✓	138.2 ✓	2.6	NOT ASSAYED		
076 B	138.2 ✓	140.2 ✓	2.0	41.49 ✓	2.98 ✓	4.25 ✓
077 B	140.2 ✓	141.7 ✓	1.5	75.77 ✓	5.81 ✓	7.52 ✓
078 B	141.7 ✓	143.3 ✓	1.6	55.54 ✓	4.28 ✓	5.55 ✓
079 B	143.3 ✓	144.8 ✓	1.5	14.06 ✓	0.22 ✓	0.60 ✓
080 B	144.8 ✓	146.3 ✓	1.5	19.20 ✓	0.65 ✓	0.50 ✓
081 B	146.3 ✓	148.3 ✓	2.0	21.26 ✓	0.56 ✓	0.58 ✓
082 B	148.3 ✓	149.7 ✓	1.4	29.14 ✓	1.50 ✓	0.95 ✓
083 B	149.7 ✓	150.5 ✓	0.8	56.57 ✓	4.05 ✓	6.01 ✓
	150.5 ✓	169.1 ✓	18.6	NOT ASSAYED		
084 B	169.1 ✓	170.7 ✓	1.6	8.91 ✓	0.70 ✓	0.75 ✓
	170.7 ✓	182.9 ✓	12.2	0.00 ✓	0.00 ✓	0.00 ✓

LATITUDE 7N

DIP AT CORNER

DEPARTURE 82W

BEARING

ELEVATION

LENGTH 182.9m (600ft)

 $0.0 - 3.0 = 3.0\text{m (10ft)}$  Ag 58.08 g/t.

Pb 2.69% Zn 5.44%

 $35.1 - 38.1 = 3.0\text{m (10ft)}$  Ag 50.92 g/t.

Pb 3.3% Zn 4.62%

 $114.0 - 120.4 = 6.4\text{m (21ft)}$ 

Ag 53.29 g/t.

Pb 3.17%

Zn 4.29%

 $138.2 - 143.3 = 5.1\text{m (16.7ft)}$ 

Ag 55.98 g/t. Pb 4.22%

Zn 5.51%

 $149.7 - 150.5 = 0.8\text{m (2.6ft)}$  Ag 56.57 g/t

Pb 4.05% Zn 6.01%

(E.C.J.)

1.9.76 - 2.9.76

ASSAY NUMBER	SECTION		CORE LENGTH	ASSAYS		
	FROM (m)	TO (m)		Ag g/t	Pb %	Zn %
4891	0.0 ✓	3.0 ✓	3.0	7.20 ✓	0.14 ✓	0.78 ✓
4892	3.0 ✓	4.6 ✓	1.6	22.29 ✓	0.78 ✓	1.28 ✓
4893	4.6 ✓	6.1 ✓	1.5	29.14 ✓	1.63 ✓	2.68 ✓
	6.1 ✓	11.6 ✓	5.5	NOT ASSAYED		
4894	11.6 ✓	12.7 ✓	1.1	84.69 ✓	5.89 ✓	7.30 ✓
	12.7 ✓	32.0 ✓	19.3	NOT ASSAYED		
4895	32.0 ✓	33.5 ✓	1.5	73.71 ✓	5.40 ✓	9.49 ✓
4896	33.5 ✓	35.1 ✓	1.6	68.57 ✓	4.73 ✓	6.76 ✓
4897	35.1 ✓	36.6 ✓	1.5	68.57 ✓	4.65 ✓	7.92 ✓
4898	36.6 ✓	38.1 ✓	1.5	69.60 ✓	4.05 ✓	4.25 ✓
4899	38.1 ✓	39.6 ✓	1.5	82.63 ✓	4.51 ✓	6.41 ✓
4900	39.6 ✓	41.1 ✓	1.5	66.51 ✓	3.80 ✓	6.24 ✓
021 B	41.1 ✓	42.7 ✓	1.6	73.71 ✓	4.30 ✓	6.93 ✓
022 B	42.7 ✓	44.2 ✓	1.5	87.77 ✓	6.00 ✓	10.81 ✓
023 B	44.2 ✓	45.7 ✓	1.5	70.63 ✓	5.40 ✓	6.74 ✓
024 B	45.7 ✓	47.2 ✓	1.5	124.12 ✓	8.70 ✓	13.62 ✓
025 B	47.2 ✓	48.8 ✓	1.6	104.92 ✓	7.03 ✓	14.71 ✓
	48.8 ✓	61.8 ✓	13.0	0.00	0.00	0.00

LATITUDE 2N

DEPARTURE 64W

ELEVATION

DIP AT COLLAR +38°

BEARING 224°

DEPTH 61.8 m (203 ft)

11.6 - 12.7 = 1.1 m (3.6 ft) Ag 84.69 g/t, Pb 5.89%, Zn 7.30%

32.0 - 48.8 = 16.8 m (55 ft)

Ag 81.6 g/t

Pb 5.32%

Zn 8.54%



ASSAY NUMBER	SECTION		CORE LENGTH	ASSAYS		
	FROM (m)	TO (m)		Ag g/t	Pb %	Zn %
B 152	0.0	1.8	1.8	161.49	7.51	19.38
B 153	1.8	3.7	1.9	48.34	2.58	8.03
B 154	3.7	4.6	0.9	63.43	3.40	7.47
B 155	4.6	6.1	1.5	74.74	4.73	10.95
B 156	6.1	7.6	1.5	44.23	2.43	7.95
B 157	7.6	9.1	1.5	1.03	0.07	0.10
<del>B 157</del>	9.1	16.4	7.3	0.00	0.00	0.00
B 158	16.4	17.5	1.1	39.43	2.25	4.50
	17.5	19.6	2.1	0.00	0.00	0.00
B 159	19.6	20.6	1.0	12.00	0.40	0.73
	20.6	30.9	10.3	0.00	0.00	0.00
B 160	30.9	32.0	1.1	106.97	6.47	13.80
B 161	32.0	33.5	1.5	12.00	0.96	1.75
B 162	33.5	35.1	1.6	73.71	4.50	8.02
B 163	35.1	36.6	1.5	70.63	4.13	7.62
B 164	36.6	38.1	1.5	56.57	3.35	6.26
	38.1	115.0	76.9	0.00	0.00	0.00
324	115.0	116.5	1.5	21.26	1.15	1.43
325	116.5	118.0	1.5	79.54	4.65	7.55
326	118.0	119.5	1.5	87.77	5.00	8.68
327	119.5	121.0	1.5	85.72	5.46	8.91
328	121.0	122.5	1.5	90.86	5.45	9.03
329	122.5	124.5	2.0	96.69	5.10	7.16
	124.5	133.9	9.4	0.00	0.00	0.00
330	133.9	135.6	1.7	53.49	3.28	2.70
331	135.6	137.2	1.6	33.26	2.13	1.30
332	137.2	138.7	1.5	65.49	4.50	7.08
333	138.7	140.2	1.5	61.37	4.00	8.06
334	140.2	141.7	1.5	95.66	5.20	9.24
335	141.7	143.3	1.6	90.86	5.90	9.59
336	143.3	144.8	1.5	83.66	5.00	8.01
337	144.8	146.3	1.5	13.03	0.63	1.05
338	146.3	147.8	1.5	9.94	0.20	0.55
<del>338</del>	147.8	150.0	2.2	0.00	0.00	0.00
339	150.0	150.9	0.9	7.20	0.10	0.18
340	150.9	152.4	1.5	20.23	1.00	1.05
341	152.4	153.9	1.5	56.57	3.85	6.93
342	153.9	155.4	1.5	65.49	3.90	6.53
343	155.4	156.5	1.1	65.49	4.65	6.35
	156.5	166.7	10.2	0.00	0.00	0.00

LATITUDE	7N	DIP AT CORNER	
DEPARTURE	82W	BEARING	
ELEVATION		DEPTH	166.7m.

ECJ.

1.9.76 - 10.9.76

ASSAY NUMBER	SECTION		CORE LENGTH	ASSAYS		
	FROM (M)	TO (M)		Ag g/t.	Pb%	Zn%
048 B	0.0 ✓	1.5 ✓	1.5	57.60 ✓	3.08 ✓	4.50 ✓
49 B	1.5 ✓	3.0 ✓	1.5	49.37 ✓	2.53 ✓	4.30 ✓
50 B	3.0 ✓	4.6 ✓	1.6	83.66 ✓	4.50 ✓	7.77 ✓
51 B	4.6 ✓	6.1 ✓	1.5	41.49 ✓	2.38 ✓	3.25 ✓
52 B	6.1 ✓	7.6 ✓	1.5	56.57 ✓	2.60 ✓	4.90 ✓
53 B	7.6 ✓	9.1 ✓	1.5	40.46 ✓	2.03 ✓	3.85 ✓
54 B	9.1 ✓	10.7 ✓	1.6	22.29 ✓	1.30 ✓	1.43 ✓
55 B	10.7 ✓	12.2 ✓	1.5	18.17 ✓	1.20 ✓	1.50 ✓
56 B	12.2 ✓	13.7 ✓	1.5	40.46 ✓	2.55 ✓	2.80 ✓
57 B	13.7 ✓	15.2 ✓	1.5	35.31 ✓	2.03 ✓	4.00 ✓
165 B	15.2 ✓	16.8 ✓	1.6	23.31 ✓	1.38 ✓	3.00 ✓
166 B	16.8 ✓	18.3 ✓	1.5	30.17 ✓	1.65 ✓	3.75 ✓
167 B	18.3 ✓	19.8 ✓	1.5	26.40 ✓	1.60 ✓	3.68 ✓
168 B	19.8 ✓	21.3 ✓	1.5	6.17 ✓	0.43 ✓	0.95 ✓
169 B	21.3 ✓	22.9 ✓	1.6	9.94 ✓	0.60 ✓	1.23 ✓
170 B	22.9 ✓	24.4 ✓	1.5	6.17 ✓	0.28 ✓	0.90 ✓
171 B	24.4 ✓	25.9 ✓	1.5	15.09 ✓	0.90 ✓	1.20 ✓
172 B	25.9 ✓	27.4 ✓	1.5	18.17 ✓	1.13 ✓	1.85 ✓
173 B	27.4 ✓	29.0 ✓	1.6	15.09 ✓	0.93 ✓	1.33 ✓
174 B	29.0 ✓	30.5 ✓	1.5	8.23 ✓	0.50 ✓	0.58 ✓
	30.5 ✓	32.5 ✓	2.0	NOT ASSAYED		
175 B	32.5 ✓	33.5 ✓	1.0	52.46 ✓	3.25 ✓	4.45 ✓
176 B	33.5 ✓	34.7 ✓	1.2	136.12 ✓	7.88 ✓	18.48 ✓
177 B	34.7 ✓	36.3 ✓	1.6	81.60 ✓	4.38 ✓	7.55 ✓
178 B	36.3 ✓	38.4 ✓	2.1	70.63 ✓	3.90 ✓	7.20 ✓
179 B	38.4 ✓	39.9 ✓	1.5	56.57 ✓	3.88 ✓	4.95 ✓
180 B	39.9 ✓	41.4 ✓	1.5	95.66 ✓	6.00 ✓	7.22 ✓
181 B	41.4 ✓	43.0 ✓	1.6	49.37 ✓	2.50 ✓	5.63 ✓
182 B	43.0 ✓	44.5 ✓	1.5	50.40 ✓	2.95 ✓	5.30 ✓
183 B	44.5 ✓	46.0 ✓	1.5	84.69 ✓	4.28 ✓	11.31 ✓
184 B	46.0 ✓	47.6 ✓	1.6	94.63 ✓	5.40 ✓	7.16 ✓
185 B	47.6 ✓	49.1 ✓	1.5	99.77 ✓	5.90 ✓	6.64 ✓
186 B	49.1 ✓	50.6 ✓	1.5	33.31 ✓	2.20 ✓	3.95 ✓
187 B	50.6 ✓	52.1 ✓	1.5	80.57 ✓	5.65 ✓	7.37 ✓
188 B	52.1 ✓	53.6 ✓	1.5	57.60 ✓	4.05 ✓	4.35 ✓
189 B	53.6 ✓	55.2 ✓	1.6	34.29 ✓	1.65 ✓	4.10 ✓
	55.2 ✓	96.3 ✓	41.1	0.00	0.00	0.00

LATITUDE

DIP AT CORNER  $-90^\circ$ 

DEPARTURE 84W

BEARING

ELEVATION

DEPTH 96.3 m (316 ft).

$$\underline{0.0 - 9.1 = 9.1 \text{ m (30 ft.)}}$$

Ag 55.17 g/t.

Pb 2.87%

Zn 4.79%

$$\underline{32.5 - 55.2 = 22.7 \text{ m (74.5 ft.)}}$$

Ag 71.40 g/t

Pb 4.21%

Zn 6.94%

E.C.J.

2.9.76 - 3.9.76

ASSAY NUMBER	SECTION		CORE LENGTH	ASSAYS		
	FROM (M)	TO (M)		Ag g/t	Pb %	Zn %
85B	0.0 ✓	1.5 ✓	1.5	9.94 ✓	0.03 ✓	0.15 ✓
86B	1.5 ✓ 3.0 ✓	3.0 ✓	1.5	10.97 ✓	0.04 ✓	0.30 ✓
87B	3.0 ✓ 4.6 ✓	4.6 ✓	1.6	12.00 ✓	0.05 ✓	0.58 ✓
88B	4.6 ✓ 6.6 ✓	6.6 ✓	2.0	5.14 ✓	0.03 ✓	0.45 ✓
	6.6 ✓	15.1 ✓	8.5	NOT ASSAYED		
89B	15.1 ✓	16.8 ✓	1.7	27.43 ✓	1.60 ✓	1.70 ✓
90B	16.8 ✓	18.3 ✓	1.5	73.71 ✓	4.48 ✓	5.70 ✓
	18.3 ✓	30.5 ✓	12.2	0.00	0.00	0.00

LATITUDE 2N  
 DEPARTURE 62W  
 ELEVATION

DIP AT COLLAR FLAT  
 BEARING 224°  
 DEPTH 30.5 m (100 ft)

16.8 - 18.3 = 1.5 m (5 ft) Ag, 73.71 g/t, Pb, 4.48%, Zn 5.70%

ASSAY NUMBER	SECTION		CORE LENGTH	ASSAYS		
	FROM (M)	TO (M)		Ag g/c	Pb %	Zn %
<del>B344</del>	0.0 ✓	1.8 ✓	1.8	0.00 ✓	0.00	0.00
B344	1.8 ✓	3.3 ✓	1.5	146.06 ✓	<del>6.87</del> 6.87 ✓	15.93 ✓
5	3.3 ✓	4.6 ✓	1.3	175.53 ✓	<del>9.43</del> 9.43 ✓	20.32 ✓
6	4.6 ✓	6.1 ✓	1.5	85.72 ✓	4.05 ✓	6.90 ✓
7	6.1 ✓	7.2 ✓	1.1	67.54 ✓	3.80 ✓	13.66 ✓
	7.2 ✓	14.0 ✓	6.8	0.00	0.00	0.00
B348	14.0 ✓	15.2 ✓	1.2	122.06 ✓	6.89 ✓	12.60 ✓
9	15.2 ✓	16.8 ✓	1.6	146.06 ✓	7.47 ✓	13.10 ✓
B350	16.8 ✓	18.3 ✓	1.5	93.94 ✓	5.49 ✓	9.90 ✓
1	18.3 ✓	19.8 ✓	1.5	67.54 ✓	4.35 ✓	6.70 ✓
2	19.8 ✓	21.3 ✓	1.5	45.26 ✓	2.80 ✓	3.85 ✓
3	21.3 ✓	22.9 ✓	1.6	65.49 ✓	3.55 ✓	7.43 ✓
4	22.9 ✓	24.4 ✓	1.5	54.52 ✓	3.18 ✓	6.38 ✓
5	24.4 ✓	25.9 ✓	1.5	22.29 ✓	1.30 ✓	3.10 ✓
6	25.9 ✓	27.4 ✓	1.5	60.34 ✓	3.78 ✓	8.27 ✓
B366	27.4 ✓	29.0 ✓	1.6	54.51 ✓	3.60 ✓	8.09 ✓
7	29.0 ✓	30.5 ✓	1.5	19.20 ✓	1.28 ✓	2.70 ✓
8	30.5 ✓	32.0 ✓	1.5	63.43 ✓	4.50 ✓	8.25 ✓
9	32.0 ✓	33.5 ✓	1.5	82.63 ✓	5.21 ✓	9.00 ✓
B370	33.5 ✓	35.1 ✓	1.6	8.23 ✓	0.53 ✓	0.15 ✓
1	35.1 ✓	36.6 ✓	1.5	43.51 ✓	2.80 ✓	5.35 ✓
2	36.6 ✓	38.1 ✓	1.5	60.34 ✓	3.30 ✓	8.05 ✓
3	38.1 ✓	39.6 ✓	1.5	64.46 ✓	3.75 ✓	7.85 ✓
4	39.6 ✓	40.6 ✓	1.0	46.29 ✓	2.30 ✓	4.25 ✓
	40.6 ✓	40.9 ✓	0.3	0.00	0.00	0.00
B375	40.9 ✓	41.3 ✓	0.4	30.17 ✓	1.50 ✓	2.03 ✓
	41.3 ✓	49.2 ✓	<del>7.9</del> 7.9	0.00	0.00	0.00
B357	49.2 ✓	50.3 ✓	<del>1.1</del> 1.1	62.06 ✓	4.23 ✓	6.40 ✓
8	50.3 ✓	51.8 ✓	<del>1.5</del> 1.5	85.72 ✓	6.23 ✓	8.84 ✓
9	51.8 ✓	53.3 ✓	<del>1.5</del> 1.5	89.83 ✓	6.28 ✓	9.24 ✓
B360	53.3 ✓	54.9 ✓	<del>1.6</del> 1.6	61.37 ✓	4.00 ✓	8.76 ✓
1	54.9 ✓	56.4 ✓	<del>1.5</del> 1.5	55.54 ✓	3.28 ✓	7.50 ✓
2	56.4 ✓	57.9 ✓	<del>1.5</del> 1.5	41.49 ✓	2.40 ✓	5.23 ✓
3	57.9 ✓	59.4 ✓	<del>1.5</del> 1.5	82.63 ✓	5.56 ✓	8.50 ✓
4	59.4 ✓	61.0 ✓	<del>1.6</del> 1.6	23.31 ✓	1.38 ✓	2.55 ✓
5	61.0 ✓	62.5 ✓	<del>1.5</del> 1.5	9.94 ✓	0.50 ✓	1.08 ✓
B376	62.5 ✓	64.0 ✓	<del>1.5</del> 1.5	12.0 ✓	0.68 ✓	1.88 ✓
7	64.0 ✓	65.0 ✓	<del>1.0</del> 1.0	8.23 ✓	0.50 ✓	1.00 ✓

LATITUDE 7N  
 DEPARTURE 82W  
 ELEVATION

DIP AT COLLAR  $-24^{\circ}$   
 BEARING  $224^{\circ}$   
 DEPTH 121.9 m.

E.C.J.

CONT'D

ASSAY NUMBER	SECTION		Core Length	Assays		
	From (m)	To (m)		Ag g/t	% Pb	% Zn
<del>B</del>	65.0 ✓	70.1 ✓	<del>15.1</del> <sup>5.1</sup>	0.00 ✓	0.00	0.00
B378	70.1 ✓	71.6 ✓	1.5	20.23 ✓	1.55 ✓	2.43
9	71.6 ✓	73.2 ✓	1.6	17.14 ✓	1.10 ✓	2.10 ✓
<del>B</del>	73.2 ✓	94.5 ✓	21.3	0.00 ✓	0.00	0.00
B380	94.5 ✓	96.0 ✓	1.5	49.37 ✓	3.43 ✓	3.90 ✓
1	96.0 ✓	97.5 ✓	1.5	35.31 ✓	3.08 ✓	4.00 ✓
2	97.5 ✓	99.1 ✓	1.6	21.26 ✓	1.13 ✓	1.20 ✓
3	99.1 ✓	100.6 ✓	1.5	17.14 ✓	0.50 ✓	0.65 ✓
4	100.6 ✓	102.1 ✓	1.5	28.11 ✓	1.20 ✓	1.15 ✓
5	102.1 ✓	103.6 ✓	1.5	44.23 ✓	4.05 ✓	4.30 ✓
6	103.6 ✓	105.2 ✓	1.6	25.37 ✓	2.18 ✓	2.05 ✓
7	105.2 ✓	106.7 ✓	1.5	27.43 ✓	1.83 ✓	3.03 ✓
8	106.7 ✓	108.2 ✓	1.5	40.46 ✓	2.30 ✓	2.15 ✓
9	108.2 ✓	109.7 ✓	1.5	10.97 ✓	0.50 ✓	1.00 ✓
B390	109.7 ✓	111.3 ✓	1.6	13.03 ✓	0.55 ✓	0.85 ✓
1	111.3 ✓	112.8 ✓	1.5	24.34 ✓	1.78 ✓	0.93 ✓
2	112.8 ✓	114.3 ✓	1.5	23.31 ✓	1.68 ✓	0.65 ✓
3	114.3 ✓	115.8 ✓	1.5	25.37 ✓	0.98 ✓	1.53 ✓
4	115.8 ✓	117.3 ✓	1.5	120.00 ✓	6.73 ✓	11.29 ✓
5	117.3 ✓	118.9 ✓	1.6	46.29 ✓	2.65 ✓	2.85 ✓
6	118.9 ✓	120.4 ✓	1.5	40.46 ✓	2.48 ✓	2.65 ✓
7	120.4 ✓	121.9 ✓	1.5	66.51 ✓	4.65 ✓	9.13 ✓
8						

3.9.76 - 4.9.76

ASSAY NUMBER.	SECTION		CORE LENGTH	ASSAYS		
	FROM (M)	TO (M)		Ag g/t	Pb %	Zn %
91B	0.0 ✓	3.0 ✓	3.0	55.54 ✓	3.10 ✓	7.48 ✓
	3.0 ✓	14.3 ✓	11.3	NOT ASSAYED		
92B	14.3 ✓	15.3 ✓	1.0	8.91 ✓	0.35 ✓	0.80 ✓
93B	15.3 ✓	18.3 ✓	3.0	7.89 ✓	0.45 ✓	0.70 ✓
	18.3 ✓	21.3 ✓	3.0	NOT ASSAYED		
94B	21.3 ✓	22.9 ✓	1.6	5.14 ✓	0.23 ✓	0.65 ✓
95B	22.9 ✓	24.4 ✓	1.5	2.06 ✓	0.05 ✓	0.38 ✓
	24.4 ✓	33.5 ✓	9.1	NOT ASSAYED		
96B	33.5 ✓	34.5 ✓	1.0	4.11 ✓	0.10 ✓	0.08 ✓
97B	34.5 ✓	36.6 ✓	2.1	21.26 ✓	1.25 ✓	0.25 ✓
98B	36.6 ✓	38.1 ✓	1.5	22.29 ✓	1.70 ✓	1.40 ✓
99B	38.1 ✓	39.6 ✓	1.5	17.14 ✓	1.63 ✓	1.25 ✓
100B	39.6 ✓	41.1 ✓	1.5	4.11 ✓	0.05 ✓	0.13 ✓
101B	41.1 ✓	42.7 ✓	1.6	15.09 ✓	0.55 ✓	0.33 ✓
102B	42.7 ✓	44.2 ✓	1.5	28.46 ✓	1.60 ✓	1.38 ✓
103B	44.2 ✓	45.7 ✓	1.5	47.31 ✓	2.40 ✓	2.00 ✓
104B	45.7 ✓	47.2 ✓	1.5	14.06 ✓	0.50 ✓	0.28 ✓
105B	47.2 ✓	48.8 ✓	1.6	21.26 ✓	1.03 ✓	0.75 ✓
106B	48.8 ✓	50.3 ✓	1.5	19.20 ✓	1.35 ✓	1.55 ✓
	50.3 ✓	51.8 ✓	1.5	NOT ASSAYED		
107B	51.8 ✓	54.0 ✓	2.2	8.23 ✓	0.28 ✓	0.38 ✓
	54.0 ✓	57.9 ✓	3.9	0.00	0.00	0.00

LATITUDE 2N

DEPARTURE 62W

ELEVATION

DIP AT COLLAR - 53°

BEARING

DEPTH 57.9 m (190 ft)

0.0 - 3.0 = 3.0m (10ft) Ag. 55.54 g/t Pb 3.10% Zn 7.48%

E.C.J.

4.9.76 - 4.9.76

ASSAY NUMBER	SECTION		CORE LENGTH	ASSAYS		
	FROM (M)	TO (M)		Ag g/t	Pb %	Zn %
	0.0 ✓	18.3 ✓	18.3	0.00	0.00	0.00
B437	18.3 ✓	20.3 ✓	2.0	40.46 ✓	2.98 ✓	4.85 ✓
	20.3 ✓	26.5 ✓	6.2	0.00	0.00	0.00
B438	26.5 ✓	28.0 ✓	1.5	39.43	2.28	4.90 ✓

MAGNITUDE  
DEPARTURE  
ELEVATION

7N  
82W

DIP AT COLLAR  
BEARING  
DEPTH

+90°

28.0m

4.9.76 - 4.9.76

ASSAY NUMBER	SECTION		CORE LENGTH	ASSAYS		
	FROM (M)	TO (M)		Ag g/t	Pb %	Zn %
128 B	0.0 ✓	1.2 ✓	1.2	12.00 ✓	0.13 ✓	0.73 ✓
129 B	1.2 ✓	2.7 ✓	1.5	10.97 ✓	0.25 ✓	1.50 ✓
130 B	2.7 ✓	4.6 ✓	1.9	8.23 ✓	0.10 ✓	0.38 ✓
131 B	4.6 ✓	6.1 ✓	1.5	9.94 ✓	0.08 ✓	0.68 ✓
	6.1 ✓	42.7 ✓	36.6	NOT ASSAYED		
132 B	42.7 ✓	43.7 ✓	1.0	10.97 ✓	0.58 ✓	0.30 ✓
133 B	43.7 ✓	44.6 ✓	0.9	53.49 ✓	3.43 ✓	4.40 ✓
134 B	44.6 ✓	45.6 ✓	1.0	20.23 ✓	1.08 ✓	0.90 ✓
	45.6 ✓	53.3 ✓	7.7	0.00	0.00	0.00

WAZITUDE 2N  
 DEPARTURE 62W  
 ELEVATION

DIP AT COLLAR -39°  
 BEARING  
 DEPTH 53.3m (175ft)

43.7 - 44.6 = 0.9m (5ft) Ag. 53.49g/t, Pb. 3.43%, Zn 4.40%.

ECJ.

ASSAY NUMBER	SECTION		CORE LENGTH	ASSAYS		
	FROM (M)	TO (M)		Ag g/t	Pb %	Zn %
	0.0 ✓	28.0 ✓	28.0	0.00	0.00	0.00
B455	28.0 ✓	30.8 ✓	2.8	80.57 ✓	4.00 ✓	8.04 ✓
	30.8 ✓	58.5 ✓	27.7	0.00 ✓	0.00 ✓	0.00 ✓
B456	58.5 ✓	60.6 ✓	2.1	67.54 ✓	4.88 ✓	8.33 ✓
B457	60.6 ✓	62.8 ✓	2.2	44.23 ✓	2.55 ✓	3.80 ✓
	62.8 ✓	109.7 ✓	46.9	0.00	0.00	0.00
B494	109.7 ✓	111.3 ✓	<del>1.6</del> 1.6	12.00 ✓	0.55 ✓	1.08 ✓
B495	111.3 ✓	112.8 ✓	<del>1.5</del> 1.5	14.06 ✓	0.70 ✓	0.95 ✓
B496	112.8 ✓	114.3 ✓	<del>1.5</del> 1.5	20.23 ✓	1.00 ✓	0.83 ✓
B497	114.3 ✓	115.8 ✓	<del>1.5</del> 1.5	34.29 ✓	1.80 ✓	3.03 ✓
B498	115.8 ✓	117.3 ✓	<del>1.5</del> 1.5	72.69 ✓	5.25 ✓	7.51 ✓
	117.3 ✓	150.8 ✓	33.5	0.00	0.00	0.00
B499	150.8 ✓	152.4 ✓	1.6	72.69 ✓	4.23 ✓	6.87 ✓
B500	152.4 ✓	153.9 ✓	1.5	102.86 ✓	5.49 ✓	7.93 ✓
B601	153.9 ✓	155.4 ✓	1.5	75.77 ✓	5.33 ✓	7.04 ✓
B602	155.4 ✓	157.0 ✓	1.6	48.34 ✓	2.95 ✓	4.05 ✓
B603	157.0 ✓	158.5 ✓	1.5	29.14 ✓	1.63 ✓	1.78 ✓
B604	158.5 ✓	160.0 ✓	1.5	41.49 ✓	2.60 ✓	3.80 ✓
B605	160.0 ✓	162.0 ✓	2.0	69.60 ✓	4.68 ✓	9.37 ✓
	162.0 ✓	170.7 ✓	8.7	0.00	0.00	0.00

LATITUDE 7N S  
 DEPARTURE 84W  
 ELEVATION

DIP AT COLLAR -70°  
 BEARING 224°  
 DEPTH 170.7m.

E.C.J.

5.9.76 - 5.9.76

ASSAY NUMBER	SECTION		CORE LENGTH	ASSAYS		
	FROM (M)	TO (M)		Ag g/t	Pb %	Zn %
B 135	0.0 ✓	3.0 ✓	3.0	8.91 ✓	0.15 ✓	0.45 ✓
136	3.0 ✓	4.6 ✓	1.6	20.23 ✓	1.21 ✓	0.98 ✓
137	4.6 ✓	6.1 ✓	1.5	16.11 ✓	0.94 ✓	1.43 ✓
138	6.1 ✓	7.6 ✓	1.5	15.09 ✓	0.65 ✓	0.60 ✓
139	7.6 ✓	10.7 ✓	3.1	10.97 ✓	0.30 ✓	0.85 ✓
140	10.7 ✓	13.7 ✓	3.0	8.91 ✓	0.14 ✓	0.58 ✓
141	13.7 ✓	16.7 ✓	3.0	13.03 ✓	0.49 ✓	0.63 ✓
142	16.7 ✓	19.7 ✓	3.0	10.97 ✓	0.35 ✓	0.35 ✓
	19.7 ✓	30.5 ✓	10.8	NOT ASSAYED		
B 143	30.5 ✓	33.5 ✓	3.0	6.17 ✓	0.08 ✓	0.18 ✓
	33.5 ✓	36.6 ✓	3.1	NOT ASSAYED		
B 144	36.6 ✓	38.1 ✓	1.5	34.29 ✓	2.68 ✓	3.35 ✓
145	38.1 ✓	39.6 ✓	1.5	9.94 ✓	0.58 ✓	1.30 ✓
	39.6 ✓	42.7 ✓	3.1	NOT ASSAYED		
B 146	42.7 ✓	44.2 ✓	1.5	5.14 ✓	0.06 ✓	0.10 ✓
	44.2 ✓	45.7 ✓	1.5	NOT ASSAYED		
B 147	45.7 ✓	47.2 ✓	1.5	13.03 ✓	0.83 ✓	0.85 ✓
148	47.2 ✓	48.8 ✓	1.6	5.14 ✓	0.10 ✓	0.08 ✓
149	48.8 ✓	50.3 ✓	1.5	38.40 ✓	2.38 ✓	3.58 ✓
150	50.3 ✓	51.8 ✓	1.5	5.14 ✓	0.08 ✓	0.18 ✓
151	51.8 ✓	53.3 ✓	1.5	5.14 ✓	0.05 ✓	0.08 ✓
	53.3 ✓	65.5 ✓	12.2	0.00	0.00	0.00

LATITUDE 2N  
 DEPARTURE 62W  
 ELEVATION

DIP AT COLLAR  
 BEARING  
 DEPTH 65.5m (215ft).

LOW

LOW

E.C.J.

ASSAY NUMBER	SECTION		CORE LENGTH	ASSAYS		
	FROM (M)	TO (M)		Ag g/t	Pb %	Zn %
606 B	0.0	4.6	4.6	60.34	4.51	7.36
607 B	4.6	6.1	1.5	35.31	2.15	4.65
608 B	6.1	7.6	1.5	28.46	1.90	4.10
609 B	7.6	9.1	1.5	74.74	4.55	10.77
610 B	9.1	10.7	1.6	87.77	5.24	9.66
611 B	10.7	12.2	1.5	33.26	2.35	3.44
612 B	12.2	13.7	1.5	23.31	1.60	1.90
613 B	13.7	15.2	1.5	5.14	0.23	0.36
614 B	15.2	16.8	1.6	29.14	2.78	0.75
615 B	16.8	18.3	1.5	37.37	3.30	1.25
(5) 616 B	18.3	20.5	2.2	0.00	0.00	0.00
616 B	20.5	22.5	2.0	45.26	3.79	2.65
	22.5	<del>23.5</del>	1.0	0.00	0.00	0.00
617 B	23.5	24.5	1.0	50.40	3.83	4.05
	24.5	25.9	1.4	0.00	0.00	0.00
618 B	25.9	29.0	3.1	36.34	2.45	3.80
	29.0	36.7	7.7	0.00	0.00	0.00
653 B	36.7	39.7	3.0	41.49	2.80	5.00
	39.7	70.1	30.4	0.00	0.00	0.00

LATITUDE 7N  
 DEPARTURE 84W  
 ELEVATION

DIP AT COLLAR +75°  
 BEARING 044°  
 DEPTH 70.1 m

5.9.76 - 6.9.76

ASSAY NUMBER	SECTION		CORE LENGTH	ASSAYS		
	FROM (M)	TO (M)		Ag g/t	Pb %	Zn %
108 B	0.0 ✓	1.5 ✓	1.5	7.20 ✓	0.05 ✓	0.20 ✓
109	1.5 ✓	3.0 ✓	1.5	14.06 ✓	0.08 ✓	0.53 ✓
110	3.0 ✓	4.6 ✓	1.6	14.06 ✓	0.38 ✓	0.88 ✓
111	4.6 ✓	6.1 ✓	1.5	30.17 ✓	2.13 ✓	2.20 ✓
112	6.1 ✓	7.6 ✓	1.5	92.92 ✓	6.54 ✓	7.24 ✓
113	7.6 ✓	9.1 ✓	1.5	105.94 ✓	7.78 ✓	9.98 ✓
114	9.1 ✓	10.7 ✓	1.6	142.49 ✓	9.63 ✓	17.24 ✓
115	10.7 ✓	12.2 ✓	1.5	100.80 ✓	6.27 ✓	16.59 ✓
	12.2 ✓	13.7 ✓	1.5	NOT ASSAYED		
116 B	13.7 ✓	15.2 ✓	1.5	144.34 ✓	9.73 ✓	23.77 ✓
117.	15.2 ✓	16.1 ✓	0.9	155.32 ✓	9.97 ✓	22.30 ✓
	16.1 ✓	17.5 ✓	1.4	NOT ASSAYED		
118 B.	17.5 ✓	18.3 ✓	0.8	42.51 ✓	2.95 ✓	4.85 ✓
	18.3 ✓	29.7 ✓	11.4	NOT ASSAYED		
119 B	29.7 ✓	32.0 ✓	2.3	85.72 ✓	5.43 ✓	11.50 ✓
120	32.0 ✓	33.5 ✓	1.5	40.46 ✓	2.33 ✓	4.90 ✓
121	33.5 ✓	35.1 ✓	1.6	10.97 ✓	0.95 ✓	2.58 ✓
122	35.1 ✓	36.6 ✓	1.5	29.14 ✓	2.28 ✓	5.72 ✓
123	36.6 ✓	38.1 ✓	1.5	59.31 ✓	3.73 ✓	5.98 ✓
124	38.1 ✓	39.6 ✓	1.5	73.71 ✓	3.98 ✓	4.55 ✓
125	39.6 ✓	41.1 ✓	1.5	39.43 ✓	2.70 ✓	3.75 ✓
126	41.1 ✓	42.7 ✓	1.6	48.34 ✓	3.68 ✓	2.55 ✓
127.	42.7 ✓	44.2 ✓	1.5	8.23 ✓	0.43 ✓	1.00 ✓
	44.2 ✓	45.7 ✓	1.5	0.00	0.00	0.00

LATITUDE 2N  
 DEPARTURE 62W,  
 ELEVATION

DIP AT COLLAR  
 BEARING +60°  
 DEPTH. 45.7m (150ft)

$6.1 - 18.3 = 12.2 \text{ m (40 ft)}$

Ag 87.8 g/t  
 Pb 5.92%  
 Zn 11.30%

$29.7 - 42.7 = 13.0 \text{ m (42.7 ft)}$

Ag 50.42 g/t  
 Pb 3.26%  
 Zn 5.54%

E.C.J.

23-9-76 to 23-9-76

Assay No.	Section		Core Length	Assays		
	From (m)	To (m)		Ag (g/t)	% Pb	% Zn
678B	0.0 ✓	3.0 ✓	3.0	35.31 ✓	2.40 ✓	4.25 ✓
679B	3.0 ✓	6.0 ✓	3.0	8.23 ✓	0.50 ✓	0.80 ✓
680B	6.0 ✓	9.0 ✓	3.0	7.20 ✓	0.40 ✓	0.73 ✓
681B	9.0 ✓	12.0 ✓	3.0	13.03 ✓	0.90 ✓	1.60 ✓
682B	x 12.0 ✓	15.0 ✓	3.0	9.94 ✓	0.87 ✓	0.55 ✓
683B	15.0 ✓	16.5 ✓	1.5	25.37 ✓	1.58 ✓	2.23 ✓
684B	16.5 ✓	18.0 ✓	1.5	35.31 ✓	2.23 ✓	2.90 ✓
685B	18.0 ✓	19.5 ✓	1.5	16.11 ✓	0.68 ✓	0.83 ✓
686B	19.5 ✓	21.0 ✓	1.5	71.66 ✓	4.78 ✓	6.84 ✓
687B	21.0 ✓	22.2 ✓	1.2	52.46 ✓	3.68 ✓	4.55 ✓
	22.2 ✓	30.5 ✓	8.7	0.00	0.00	0.00

Latitude 5N  
 Departure 84W  
 Elevation

Dip at Collar +90°  
 Brg.  
 Depth: 30.5 m.

E.C.J.

6-9-76 - 7-9-76

Assay No.	Section		Core Length	Assays		
	From(m)	To(m)		Ag g/t	Pb %	Zn %
B201	0.0 ✓	1.5 ✓	1.5	78.86 ✓	6.12 ✓	11.95 ✓
B202	1.5 ✓	3.0 ✓	1.5	129.94 ✓	8.91 ✓	16.86 ✓
B203	3.0 ✓	4.6 ✓	1.6	90.84 ✓	7.13 ✓	11.60 ✓
B204	<del>4.6</del> 6.1 ✓	6.1 ✓	1.5	78.86 ✓	4.80 ✓	9.14 ✓
B205	<del>6.1</del> 7.6 ✓	7.6 ✓	1.5	87.77 ✓	7.41 ✓	14.53 ✓
B206	<del>7.6</del> 9.1 ✓	9.1 ✓	1.5	117.94 ✓	6.31 ✓	15.14 ✓
B207	9.1 ✓	10.7 ✓	1.6	184.46 ✓	10.41 ✓	22.56 ✓
B208	10.7 ✓	11.8 ✓	1.1	171.43 ✓	10.41 ✓	20.77 ✓
	11.8 ✓	49.8 ✓	38.0	0.00	0.00	0.00
B209	49.8 ✓	51.3 ✓	1.5	91.89 ✓	5.40 ✓	9.30 ✓
B210	51.3 ✓	52.8 ✓	1.5	87.77 ✓	7.05 ✓	11.92 ✓
B211	52.8 ✓	54.3 ✓	1.5	84.69 ✓	5.70 ✓	10.16 ✓
B212	54.3 ✓	55.8 ✓	1.5	85.72 ✓	4.58 ✓	8.09 ✓
B213	55.8 ✓	57.1 ✓	1.3	37.37 ✓	2.40 ✓	5.48 ✓
B214	57.1 ✓	58.6 ✓	1.5	103.89 ✓	5.65 ✓	8.67 ✓
B215	58.6 ✓	60.4 ✓	1.8	150.17 ✓	7.80 ✓	10.21 ✓
	60.4 ✓	68.6 ✓	8.2	0.00	0.00	0.00

} Not Assayed  
Country rx

Latitude 2N  
Departure 68W  
Elev'n.

Dip at Collar  
Brg. +3°  
Depth: 68.6 m.

E.C.J.

24.9.76 - 27.9.76

Assay No.	Section		Core length	Assays		
	From (m)	To (m)		Ag g/t	Pb %	Zn %
835B	0.0 ✓	3.0 ✓	3.0	8.23 ✓	0.40 ✓	0.83 ✓
836B	3.0 ✓	5.2 ✓	2.2	9.26 ✓	0.58 ✓	0.75 ✓
	5.2 ✓	6.2 ✓	1.0	0.00 ✓	0.00 ✓	0.00 ✓
837B	6.2 ✓	9.3 ✓	3.1	52.46 ✓	3.28 ✓	5.10 ✓
838B	9.3 ✓	12.3 ✓	3.0	19.20 ✓	1.50 ✓	3.73 ✓
	12.3 ✓	20.2 ✓	7.9	0.00 ✓	0.00 ✓	0.00 ✓
839B	20.2 ✓	23.2 ✓	3.0	8.23 ✓	0.43 ✓	0.90 ✓
840B	23.2 ✓	25.0 ✓	1.8	22.29 ✓	1.23 ✓	2.28 ✓
	25.0 ✓	51.8 ✓	26.8	0.00 ✓	0.00 ✓	0.00 ✓
844B	51.8 ✓	54.9 ✓	3.1	28.46 ✓	1.50 ✓	2.00 ✓
845B	54.9 ✓	56.4 ✓	1.5	90.86 ✓	4.90 ✓	10.32 ✓
<del>846B</del>	56.4 ✓	59.4 ✓	3.0	0.00 ✓	0.00 ✓	0.00 ✓
846B	59.4 ✓	61.0 ✓	1.6	100.80 ✓	4.80 ✓	9.39 ✓
847B	61.0 ✓	62.5 ✓	1.5	55.54 ✓	3.28 ✓	7.57 ✓
848B	62.5 ✓	64.0 ✓	1.5	126.17 ✓	8.75 ✓	14.65 ✓
<del>849B</del>	64.0 ✓	65.5 ✓	1.5	104.92 ✓	6.00 ✓	10.27 ✓
850B	65.5 ✓	67.0 ✓	1.5	89.83 ✓	4.63 ✓	8.18 ✓
851B	67.0 ✓	68.5 ✓	1.5	68.57 ✓	4.48 ✓	5.22 ✓
852B	68.5 ✓	71.0 ✓	2.5	111.09 ✓	6.75 ✓	12.50 ✓
	71.0 ✓	142.5 ✓	71.5	0.00 ✓	0.00 ✓	0.00 ✓
853B	142.5 ✓	143.8 ✓	1.3	85.72 ✓	5.00 ✓	8.93 ✓
	143.8 ✓	153.6 ✓	9.8	0.00 ✓	0.00 ✓	0.00 ✓

Latitude 3N  
 Departure ~~1.23~~ 84W  
 Elev'n.

Dip at Collar: -90°  
 Brg.  
 Depth: 153.6 m

E.C.J.

7.9.76 - 8.9.76.

Assay No.	Section		Core Length	Assays		
	From(m)	To(m)		Ag(g/t)	Pb %	Zn%
B216	0.0 ✓	1.5 ✓	1.5	110.06 ✓	6.27 ✓	13.71 ✓
B217	1.5 ✓	3.0 ✓	1.5	47.31 ✓	3.50 ✓	2.55 ✓
B218	3.0 ✓	4.5 ✓	1.5	30.17 ✓	1.68 ✓	2.55 ✓
B219	4.5 ✓	6.0 ✓	1.5	35.31 ✓	2.13 ✓	4.00 ✓
B220	6.0 ✓	7.5 ✓	1.5	43.54 ✓	3.33 ✓	3.65 ✓
B221	7.5 ✓	8.5 ✓	1.0	22.29 ✓	1.05 ✓	2.45 ✓
B222	8.5 ✓	9.7 ✓	1.2	70.63 ✓	6.11 ✓	8.16 ✓
B223	9.7 ✓	11.2 ✓	1.5	76.80 ✓	5.91 ✓	11.75 ✓
B224	11.2 ✓	12.7 ✓	1.5	103.89 ✓	7.46 ✓	14.83 ✓
B225	<del>#</del> 12.7 ✓	14.2 ✓	1.5	114.17 ✓	7.28 ✓	12.71 ✓
B226	14.2 ✓	15.7 ✓	1.5	67.54 ✓	3.80 ✓	7.95 ✓
B227	15.7 ✓	17.2 ✓	1.5	69.60 ✓	4.98 ✓	8.08 ✓
B228	17.2 ✓	18.7 ✓	1.5	74.74 ✓	5.68 ✓	12.05 ✓
B229	18.7 ✓	20.2 ✓	1.5	134.06 ✓	7.61 ✓	21.12 ✓
B230	20.2 ✓	21.8 ✓	1.6	151.20 ✓	8.72 ✓	19.99 ✓
	21.8 ✓	76.2 ✓	54.4	0.00	0.00	0.00

Latitude: 2N

Departure: 68W

Elev'n:

Dip at Collar

Brg.

Depth: 76.2 m.

27.9.76 - 30.9.76.

Assay No.	Section		Core Length	Assays		
	From(m)	To(m)		Ag g/t	Pb%	Zn%
864B	0.0 ✓	3.0 ✓	3.0	8.91 ✓	0.53 ✓	0.80 ✓
865B	3.0 ✓	5.0 ✓	2.0	8.91 ✓	0.58 ✓	1.55 ✓
	5.0 ✓	6.0 ✓	1.0	0.00	0.00	0.00
866B	6.0 ✓	7.5 ✓	1.5	8.91 ✓	0.58 ✓	0.48 ✓
867B	<del>7.5</del> ✓	9.0 ✓	1.5	7.20 ✓	0.55 ✓	1.03 ✓
868B	<del>9.0</del> ✓	12.0 ✓	3.0	10.97 ✓	0.75 ✓	1.25 ✓
869B	12.0 ✓	13.5 ✓	1.5	61.37 ✓	3.40 ✓	6.86 ✓
	13.5 ✓	23.2 ✓	9.7	0.00	0.00	0.00
870B	23.2 ✓	24.8 ✓	1.6	38.40 ✓	2.50 ✓	3.66 ✓
	24.8 ✓	26.1 ✓	1.3	0.00 ✓	0.00 ✓	0.00 ✓
871B	26.1 ✓	27.6 ✓	1.5	27.43 ✓	1.80 ✓	2.60 ✓
872B	27.6 ✓	29.1 ✓	1.5	25.37 ✓	1.55 ✓	3.15 ✓
873B	29.1 ✓	30.6 ✓	1.5	7.20 ✓	0.48 ✓	0.95 ✓
874B	30.6 ✓	32.1 ✓	1.5	12.00 ✓	0.65 ✓	1.08 ✓
875B	32.1 ✓	33.6 ✓	1.5	10.97 ✓	0.75 ✓	1.25 ✓
876B	33.6 ✓	35.1 ✓	1.5	5.14 ✓	0.40 ✓	0.78 ✓
877B	35.1 ✓	36.6 ✓	1.5	8.91 ✓	0.60 ✓	1.23 ✓
878B	36.6 ✓	39.6 ✓	3.0	12.00 ✓	0.85 ✓	1.28 ✓
879B	39.6 ✓	42.6 ✓	3.0	8.91 ✓	0.65 ✓	0.90 ✓
880B	42.6 ✓	45.6 ✓	3.0	9.94 ✓	0.65 ✓	1.20 ✓
881B	45.6 ✓	48.6 ✓	3.0	12.00 ✓	0.88 ✓	1.23 ✓
	48.6 ✓	50.5 ✓	1.9	0.00	0.00	0.00
882B	50.5 ✓	52.0 ✓	1.5	29.14 ✓	2.05 ✓	2.65 ✓
883B	52.0 ✓	53.5 ✓	1.5	87.77 ✓	5.78 ✓	8.93 ✓
884B	53.5 ✓	55.0 ✓	1.5	65.49 ✓	3.88 ✓	8.85 ✓
885B	55.0 ✓	56.5 ✓	1.5	71.66 ✓	4.70 ✓	11.84 ✓
886B	56.5 ✓	58.0 ✓	1.5	57.60 ✓	3.50 ✓	7.77 ✓
887B	58.0 ✓	59.3 ✓	1.3	140.23 ✓	9.86 ✓	12.34 ✓
	59.3 ✓	64.2 ✓	4.9	0.00	0.00	0.00
888B	64.2 ✓	65.8 ✓	1.6	110.06 ✓	7.90 ✓	14.06 ✓
889B	65.8 ✓	67.4 ✓	1.6	136.12 ✓	10.30 ✓	15.27 ✓
	67.4 ✓	70.1 ✓	2.7	0.00	0.00	0.00
890B	70.1 ✓	71.0 ✓	0.9	112.12 ✓	8.35 ✓	11.48 ✓
	71.0 ✓	98.0 ✓	27.0	0.00	0.00	0.00
891B	98.0 ✓	100.6 ✓	2.6	26.40 ✓	1.80 ✓	2.55 ✓
	100.6 ✓	108.5 ✓	7.9	0.00	0.00	0.00
892B	108.5 ✓	111.5 ✓	3.0	15.09 ✓	1.13 ✓	1.10 ✓
893B	111.5 ✓	113.0 ✓	1.5	32.23 ✓	2.33 ✓	3.10 ✓
894B	113.0 ✓	116.0 ✓	3.0	18.17 ✓	1.23 ✓	1.40 ✓

Latitude 3N + 13.5 N

Dip at Collar: -55°

Departure 84 ~~13.5~~ W

Brg. 224°

Elev'n:

Depth: 167.6 m

E.C.J.

CONT'D

Assay No.	Section		Core Length	Assays		
	From (m)	To (m)		Ag g/t	Pb %	Zn %
895B	116.0 ✓	119.0 ✓	3.0	15.09 ✓	1.00 ✓	1.58 ✓
	119.0 ✓	122.8 ✓	3.8	0.00	0.00	0.00
896B	122.8 ✓	125.8 ✓	3.0	25.37 ✓	1.50 ✓	1.95 ✓
897B	125.8 ✓	128.8 ✓	3.0	12.00 ✓	0.83 ✓	0.80 ✓
898B	128.8 ✓	131.8 ✓	3.0	5.14 ✓	0.13 ✓	0.18 ✓
899B	131.8 ✓	134.8 ✓	3.0	5.14 ✓	0.17 ✓	0.15 ✓
900B	134.8 ✓	136.3 ✓	1.5	14.06 ✓	0.98 ✓	1.28 ✓
901B	136.3 ✓	137.8 ✓	1.5	47.31 ✓	3.85 ✓	5.00 ✓
902B	137.8 ✓	139.3 ✓	1.5	8.32 ✓	0.45 ✓	0.63 ✓
903B	139.3 ✓	140.8 ✓	1.5	35.31 ✓	2.35 ✓	3.05 ✓
904B	140.8 ✓	142.3 ✓	1.5	63.43 ✓	5.00 ✓	7.02 ✓
905B	142.3 ✓	143.8 ✓	1.5	70.63 ✓	4.23 ✓	5.45 ✓
	143.8 ✓	167.6 ✓	23.8	0.00	0.00	0.00

8.9.76 - 9.9.76

Assay No.	Section		Core Length	Assays		
	From (m)	To (m)		Ag g/t	Pb %	Zn %
<del>B190</del>	0.0 ✓	6.1 ✓	6.1	0.00	0.00	0.00
B190	6.1 ✓	7.6 ✓	1.5	20.23	1.23	1.85
<del>B191</del> B191	7.6 ✓	9.1 ✓	1.5	93.94	6.43	14.02
<del>B192</del> B192	9.1 ✓	10.7 ✓	1.6	110.06	6.83	15.27
<del>B193</del> B193	10.7 ✓	12.2 ✓	1.5	66.51	5.86	11.84
<del>B194</del> B194	12.2 ✓	13.7 ✓	1.5	84.69	7.81	15.99
<del>B195</del> B195	13.7 ✓	15.2 ✓	1.5	84.69	6.43	11.59
<del>B196</del> B196	15.2 ✓	16.8 ✓	1.6	104.92	8.11	17.43
<del>B197</del> B197	16.8 ✓	18.3 ✓	1.5	172.46	10.47	26.45
<del>B198</del> B198	18.3 ✓	19.8 ✓	1.5	90.86	6.23	17.52
B199	19.8 ✓	20.5 ✓	0.7	141.20	9.69	20.65
	20.5 ✓	<del>58.6</del> <sup>57.9</sup> ✓	37.4	0.00	0.00	0.00
B301	57.9 ✓	58.6 ✓	0.7	80.57	5.50	9.70
	58.6 ✓	91.4 ✓	32.8	0.00	0.00	0.00

Latitude 2N  
 Departure 67W  
 Elev'n:

Dip at Collar  
 no. Brg.  
 Depth. 91.4 m.

E.C.J.

30.9.76 - 1.10.76

Assay No.	Section		Core Length	Assays		
	From (m)	To (m)		Ag %	Pb %	Zn %
906B	0.0 ✓	3.0 ✓	3.0	6.17 ✓	0.38 ✓	0.53 ✓
907B	3.0 ✓	6.0 ✓	3.0	14.06 ✓	0.98 ✓	1.15 ✓
908B	6.0 ✓	9.0 ✓	3.0	8.91 ✓	0.58 ✓	0.98 ✓
909B	9.0 ✓	11.5 ✓	2.5	21.26 ✓	1.43 ✓	2.90 ✓
	11.5 ✓	61.0 ✓	49.5	0.00	0.00	0.00

Latitude 3N+14m  
 Departure 84 W.  
 Elev'n.

Dip at Collar +70°  
 Brg. 224°  
 Depth 61.0 m

9.9.76 - 10.9.76.

Assay No.	Section		Core Length	Assays		
	From (m)	To (m)		Ag g/t	Pb %	Zn %
	0.0 ✓	16.8 ✓	16.8	0.00	0.00	0.00
B302	16.8 ✓	18.3 ✓	1.5	4.11 ✓	0.10 ✓	0.70 ✓
B303	18.3 ✓	19.8 ✓	1.5	15.09 ✓	0.43 ✓	0.78 ✓
B304	19.8 ✓	21.3 ✓	1.5	20.23 ✓	1.48 ✓	2.85 ✓
B305	21.3 ✓	22.9 ✓	1.6	40.46 ✓	3.05 ✓	3.55 ✓
B306	22.9 ✓	24.4 ✓	1.5	17.14 ✓	1.23 ✓	1.33 ✓
B307	24.4 ✓	25.9 ✓	1.5	15.09 ✓	1.10 ✓	1.48 ✓
B308	25.9 ✓	27.4 ✓	1.5	20.23 ✓	1.93 ✓	1.85 ✓
B309	27.4 ✓	29.0 ✓	1.6	31.20 ✓	0.98 ✓	2.05 ✓
B310	29.0 ✓	30.5 ✓	1.5	8.23 ✓	0.60 ✓	1.33 ✓
B311	30.5 ✓	32.0 ✓	1.5	22.29 ✓	1.63 ✓	2.93 ✓
B312	32.0 ✓	33.5 ✓	1.5	14.06 ✓	1.03 ✓	1.68 ✓
B313	33.5 ✓	35.1 ✓	1.6	9.94 ✓	0.33 ✓	1.25 ✓
	35.1 ✓	45.7 ✓	10.6	0.00	0.00	0.00
B314	45.7 ✓	47.2 ✓	1.5	7.20 ✓	0.47 ✓	4.90 ✓
B315	47.2 ✓	48.8 ✓	1.6	5.14 ✓	0.05 ✓	1.33 ✓
B316	48.8 ✓	50.3 ✓	1.5	5.14 ✓	0.03 ✓	0.93 ✓
B317	50.3 ✓	51.8 ✓	1.5	9.94 ✓	0.04 ✓	2.35 ✓
B318	51.8 ✓	53.3 ✓	1.5	8.23 ✓	0.04 ✓	5.00 ✓
B319	53.3 ✓	54.9 ✓	1.6	8.91 ✓	0.10 ✓	2.13 ✓
B320	54.9 ✓	56.4 ✓	1.5	12.00 ✓	0.09 ✓	2.08 ✓
B321	56.4 ✓	57.9 ✓	1.5	10.97 ✓	0.13 ✓	1.95 ✓
B322	57.9 ✓	59.4 ✓	1.5	8.91 ✓	0.28 ✓	1.80 ✓
B323	59.4 ✓	60.3 ✓	0.9	42.51 ✓	1.95 ✓	3.98 ✓
	60.3 ✓	91.4 ✓	31.1	0.00	0.00	0.00

Latitude  
Departure  
Elev'n.

2N  
67W

Dip at Collar: -45°  
Brg.  
Depth: 91.4 m.

3.10.76 - 4.10.76

Latitude 3N  
Departure 82W  
Elev'n:

Dip at Collar: 0°  
Brg: 44°  
Depth: 83.8 m

Assay No.	Section		Core length	Assays		
	From(m)	To(m)		Ag g/t	Pb %	Zn %
	0.0 ✓	3.0 ✓	3.0	0.00	0.00	0.00
945 B	3.0 ✓	6.0 ✓	3.0	13.03 ✓	0.98 ✓	2.10 ✓
946 B	6.0 ✓	9.0 ✓	3.0	8.91 ✓	0.73 ✓	1.48 ✓
	9.0 ✓	15.2 ✓	6.2	0.00	0.00	0.00
947 B	15.2 ✓	16.7 ✓	1.5	21.26 ✓	<del>1.38</del> 1.38 ✓	2.98 ✓
948 B	16.7 ✓	18.2 ✓	1.5	32.23 ✓	2.18 ✓	3.65 ✓
949 B	18.2 ✓	19.7 ✓	1.5	40.46 ✓	2.78 ✓	5.00 ✓
950 B	19.7 ✓	21.2 ✓	1.5	33.26 ✓	2.28 ✓	4.05 ✓
991 B	21.2 ✓	22.7 ✓	1.5	27.43 ✓	1.78 ✓	3.33 ✓
992 B	22.7 ✓	24.2 ✓	1.5	50.40 ✓	3.58 ✓	5.90 ✓
993 B	24.2 ✓	27.2 ✓	3.0	7.20 ✓	0.45 ✓	0.85 ✓
994 B	27.2 ✓	30.2 ✓	3.0	8.23 ✓	0.50 ✓	0.63 ✓
995 B	30.2 ✓	33.2 ✓	3.0	9.94 ✓	0.35 ✓	0.70 ✓
996 B	33.2 ✓	36.2 ✓	3.0	19.20 ✓	0.68 ✓	1.30 ✓
997 B	36.2 ✓	39.2 ✓	3.0	8.23 ✓	0.40 ✓	0.93 ✓
998 B	39.2 ✓	42.2 ✓	3.0	12.00 ✓	0.93 ✓	1.68 ✓
999 B	42.2 ✓	45.0 ✓	2.8	31.20 ✓	1.88 ✓	3.75 ✓
	45.0 ✓	56.0 ✓	11.0	0.00	0.00	0.00
1000 B	56.0 ✓	<del>57.9</del> <del>83.8</del>	<del>1.9</del> <del>27.8</del>	8.91 ✓	0.68 ✓	0.90 ✓
	57.9 ✓	83.8 ✓	25.9	0.00	0.00	0.00

10.9.76 - 12.9.76

Assay No.	Section		Core Length	Assays		
	From (m)	To (m)		Ag g/t	Pb %	Zn %
	0.0 ✓	36.6 ✓	36.6	0.00	0.00	0.00
B398	36.6 ✓	38.1 ✓	1.5	4.11 ✓	0.04 ✓	0.10 ✓
B399	38.1 ✓	39.6 ✓	1.5	3.09 ✓	0.04 ✓	0.05 ✓
	39.6 ✓	46.0 ✓	6.4	0.00	0.00	0.00
B400	46.0 ✓	47.2 ✓	1.2	2.06 ✓	0.03 ✓	0.20 ✓
B401	47.2 ✓	48.8 ✓	1.6	2.06 ✓	0.02 ✓	0.08 ✓
B402	48.8 ✓	50.3 ✓	1.5	<del>2.06</del> 3.09 ✓	0.05 ✓	0.20 ✓
B403	50.3 ✓	51.8 ✓	1.5	3.09 ✓	0.05 ✓	0.15 ✓
B404	51.8 ✓	53.3 ✓	1.5	3.09 ✓	0.03 ✓	0.13 ✓
B405	53.3 ✓	54.9 ✓	1.6	5.14 ✓	0.05 ✓	0.38 ✓
B406	54.9 ✓	56.4 ✓	1.5	1.03 ✓	0.01 ✓	0.50 ✓
B4087	56.4 ✓	58.4 ✓	2.0	32.23 ✓	2.65 ✓	5.40 ✓
B408	58.4 ✓	60.4 ✓	2.0	21.26 ✓	1.18 ✓	3.40 ✓
B409	60.4 ✓	61.0 ✓	0.6	25.37 ✓	1.05 ✓	1.80 ✓
B410	61.0 ✓	62.5 ✓	1.5	3.09 ✓	0.18 ✓	1.10 ✓
	62.5 ✓	82.9 ✓	20.4	0.00	0.00	0.00
B411	82.9 ✓	85.3 ✓	2.4	29.14 ✓	3.20 ✓	1.80 ✓
B412	85.3 ✓	87.5 ✓	2.2	16.11 ✓	1.08 ✓	0.85 ✓
B413	87.5 ✓	88.4 ✓	0.9	14.06 ✓	0.55 ✓	0.90 ✓
B414	88.4 ✓	89.9 ✓	1.5	18.17 ✓	1.03 ✓	1.43 ✓
B415	89.9 ✓	90.8 ✓	0.9	17.14 ✓	1.25 ✓	1.23 ✓
B416	90.8 ✓	93.0 ✓	2.2	27.43 ✓	1.85 ✓	2.15 ✓
B417	93.0 ✓	93.9 ✓	0.9	12.00 ✓	1.05 ✓	1.43 ✓
B418	93.9 ✓	95.4 ✓	1.5	8.23 ✓	0.40 ✓	0.38 ✓
B419	95.4 ✓	96.3 ✓	0.9	5.14 ✓	0.53 ✓	0.85 ✓
B420	96.3 ✓	97.8 ✓	1.5	6.17 ✓	0.55 ✓	0.98 ✓
B421	97.8 ✓	100.3 ✓	2.5	24.34 ✓	2.78 ✓	2.13 ✓
B422	100.3 ✓	101.8 ✓	1.5	32.23 ✓	3.68 ✓	2.03 ✓
B423	101.8 ✓	103.6 ✓	1.8	20.23 ✓	1.85 ✓	1.20 ✓
B424	103.6 ✓	105.2 ✓	1.6	29.14 ✓	2.48 ✓	2.63 ✓
B425	105.2 ✓	106.7 ✓	1.5	67.84 ✓	4.45 ✓	4.95 ✓
B426	106.7 ✓	108.2 ✓	1.5	25.37 ✓	1.53 ✓	1.13 ✓
B427	108.2 ✓	109.7 ✓	1.5	15.09 ✓	1.03 ✓	0.83 ✓
B428	109.7 ✓	111.3 ✓	1.6	9.94 ✓	0.30 ✓	0.33 ✓
B429	111.3 ✓	112.8 ✓	1.5	9.94 ✓	0.25 ✓	0.35 ✓
B430	112.8 ✓	114.3 ✓	1.5	36.34 ✓	2.03 ✓	2.65 ✓
B431	114.3 ✓	115.8 ✓	1.5	7.20 ✓	0.38 ✓	0.45 ✓
B432	115.8 ✓	117.3 ✓	1.5	12.00 ✓	0.20 ✓	0.35 ✓
B433	117.3 ✓	118.9 ✓	1.6	5.14 ✓	0.10 ✓	0.20 ✓

