



K 105K03/1245
VOL 1 UNC
Cyprus Anvil Mining Corporation

1977/01/01 1981/01/01

ASSAY CERTS
DY-1979, 1980
= 1981

014942

1981



Member
Canadian Testing
Association

KAMLOOPS RESEARCH & ASSAY LABORATORY LTD.

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS B.C.
V1S 1A7

PHONE: (604) 372-2784 — TELEX: 048-8320

CERTIFICATE OF ASSAY

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS
METALLURGISTS

TO Cyprus Anvil Mining Corporation Ltd.
330 - 355 Burrard Street
Vancouver, B.C. V6C 2G8

Certificate No. K-3997


Date May 14, 1981

401

I hereby certify that the following are the results of assays made by us upon the herein described _____ samples

Kral No.	Marked	Ag	Pb	Zn	Cu					
		grams per tonne	percent	percent	percent					
1	1998	70	4.45	5.57	.10					
2	1999	51	2.79	3.33	.12					
3	2000	5	.10	.24	.11					
4	2043	6	.11	.36	.10					
5	2044	7	.13	.22	.14					
6	2045	26	.69	.58	.27					
7	2046	13	.28	.23	.10					
8	2047	34	1.64	.94	.28					
9	2048	32	1.49	.60	.31					
10	2049	28	.76	.26	.46					
11	2050	27	1.16	.49	.35					
12	2401	37	1.95	.55	.22					
13	2402	30	1.26	.78	.31					

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.


Registered Assayer, Province of British Columbia



Member
Canadian Testing
Association

KAMLOOPS RESEARCH & ASSAY LABORATORY LTD.

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS B.C.
V1S 1A7

PHONE: (604) 372-2784 — TELEX: 048-8320

CERTIFICATE OF ASSAY

**B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS
METALLURGISTS**

TO Cyprus Anvil Mining Corporation Ltd.
330 - 355 Burrard Street
Vancouver, B.C. V6C 2G8

Certificate No. K-3964

Date May 11, 1981

I hereby certify that the following are the results of assays made by us upon the herein described _____ samples

Kral No.	Marked	Ag	Pb	Zn	Cu					
		grams per tonne	percent	percent	percent					
1	1961	38	2.60	3.40	.17	SA Dump Hale				81-VX-01
2	1962	76	5.10	11.00	.12					
3	1963	42	3.20	3.20	.21					
4	1964	36	1.91	2.80	.11					
5	1965	47	3.20	2.90	.19					
6	1966	49	3.60	3.20	.18					
7	1967	53	3.80	3.50	.22					
8	1968	28	1.41	.91	.14					
9	1969	4	.23	.19	.09	X-02				
10	1970	58	4.20	7.10	.11					
11	1971	49	4.30	7.00	.07					
12	1972	30	3.30	2.02	.14					
13	1973	29	3.20	2.30	.06					
14	1974	32	.15	.04	.08					
15	1975	13	.41	.43	.13					
16	1976	9	.28	.51	.13					
17	1977	7	.35	1.23	.05					
18	1978	6	.23	1.10	.05					
19	1979	8	.24	.39	.03					
20	1980	19	.98	.41	.20					

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.

Registered Assayer, Province of British Columbia



Member
Canadian Testing
Association

KAMLOOPS RESEARCH & ASSAY LABORATORY LTD.

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS B.C.

V1S 1A7

PHONE: (604) 372-2784 — TELEX: 048-8320

CERTIFICATE OF ASSAY

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS
METALLURGISTS

TO Cyprus Anvil Mining Corporation Ltd.

Certificate No. K-3964 2

Date May 11, 1981

I hereby certify that the following are the results of assays made by us upon the herein described _____ samples

Kral No.	Marked	Ag	Pb	Zn	Cu					
		grams per tonne	percent	percent	percent					
21	1981	5	.03	.06	.05					
22	1982	7	.09	.24	.01					
23	1983	5	.19	.43	.04					
24	1984	4	.07	.06	.03					
25	1985	6	.02	.03	.38					
26	1986	4	.01	.02	.18					
27	1987	4	.04	.01	.08					
28	1988	4	.05	.14	.11					
29	1989	3	.08	.17	.07					
30	1990	14	.63	.73	.12					
31	1991	36	4.60	4.60	.06					
32	1992	29	2.50	.45	.01					
33	1993	125	9.40	10.30	.01					
34	1994	18	.78	1.15	.15					
35	1995	146	8.90	10.20	.12					
36	1996	150	8.60	10.90	.20					
37	1997	8	.38	1.35	.15					

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.

Registered Assayer, Province of British Columbia



KAMLOOPS RESEARCH & ASSAY LABORATORY LTD.

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS B.C.
V1S 1A7

PHONE: (604) 372-2784 — TELEX: 048-8320

CERTIFICATE OF ASSAY

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS
METALLURGISTS

TO Cyprus Anvil Mining Corporation Ltd.
330 - 355 Burrard Street
Vancouver, B.C. V6C 2G8

Certificate No. K-4126

Date June 11, 1981

I hereby certify that the following are the results of assays made by us upon the herein described DY Core samples

Kral No.	Marked	Ag	Pb	Zn	Cu				
		grams per tonne	percent	percent	percent				
1	2403	44	2.73	1.46	.07				
2	2404	32	1.70	1.64	.13				
3	2405	59	3.56	1.67	.13				
4	2406	46	2.90	1.89	.26				
5	2407	20	1.06	.71	.04				
6	2408	17	.85	1.29	.05				
7	2409	11	.37	.15	.06				
8	2410	32	.51	.15	.39				
9	2411	26	.92	.65	.15				
10	2412	12	.52	.26	.04				
11	2413	9	.32	.05	.08				
12	2414	8	.27	.02	.07				
13	2415	13	.18	.49	.19				
14	2416	6	.07	.16	.11				
15	2417	4	.02	.03	.05				
16	2418	2	.03	.03	.08				
17	2419	2	.02	.02	.02				
18	2420	1	.03	.04	.04				
19	2421	1	.01	.02	.03				
20	2422	8	.06	.08	.17				

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.

Registered Assayer, Province of British Columbia



Member
Canadian Testing
Association

KAMLOOPS RESEARCH & ASSAY LABORATORY LTD.

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS B.C.
V1S 1A7

PHONE: (604) 372-2784 — TELEX: 048-8320

CERTIFICATE OF ASSAY

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS
METALLURGISTS

TO Cyprus Anvil Mining Corporation Ltd.
330 - 355 Burrard Street
Vancouver, B.C. V6C 2G8

403

Certificate No. K-4178

Date June 30, 1981

CHECKS

I hereby certify that the following are the results of assays made by us upon the herein described Grum Core samples

Kral No.	Marked	Ag	Pb	Zn	Cu				
		grams per tonne	percent	percent	percent				
1	2436	49	3.38	1.87	.33				
2	2437	46	3.28	3.21	.26				
3	2438	35	2.08	2.36	.22				
4	2439	22	.55	.27	.20				
5	2440	37	1.75	1.34	.15				

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.

Dan La Ross

Registered Assayer, Province of British Columbia



KAMLOOPS RESEARCH & ASSAY LABORATORY LTD.

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS B.C.
V1S 1A7

PHONE: (604) 372-2784 — TELEX: 048-8320

CERTIFICATE OF ASSAY

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS
METALLURGISTS 6

TO Cyprus Anvil Mining Corporation

Certificate No. K-3428

Date December 19, 1980

I hereby certify that the following are the results of assays made by us upon the herein described _____ samples

Kral No.	Marked	GOLD	SILVER	Py	Po	BaO	Hg	S.G.		
		grams per tonne	grams per tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent
101	X 3530	1.10	102	13.6	1.4	28.9	.006	4.46		
102	3531	1.37	50	26.4	6.3	6.2	.002	4.39		
103	3532	1.10	76	15.6	13.3	9.2	.003	4.18		
104	3536	1.17	62	13.8	.9	15.8	.005	3.76		
105	3537	.93	42	27.3	1.9	3.3	.002	4.02		
106	3538	.82	64	12.3	1.6	17.2	.006	3.78		
107	5147	.62	115	12.8	2.6	14.6	.004	3.92		
108	5148	.30	20	4.0	3.8	2.1	.001	2.79		
109	5149	.96	65	20.4	3.6	13.8	.004	4.45		
110	X 5150	2.54	36	30.5	8.5	0.1	.001	4.22		

01

07

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.

[Signature]
Registered Assayer, Province of British Columbia



Kamloops Research & Assay Laboratory Ltd.

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS, B.C. V1S 1A7
TELEPHONE 372-2784 TELEEX 048-8320

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS

CERTIFICATE OF ASSAY

TO Cyprus Anvil Mining Corporation

330 - 355 Burrard St.

Vancouver, B.C. V6C 2G8

Attention: Dr. G. Simpson
cc Darryl Hanson

Certificate No. K-2704

Date May 1, 1980

I hereby certify that the following are the results of assays made by us upon the herein described drill core samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		Ounces Per Ton	Ounces Per Ton	Percent	Percent	Percent	Percent	Percent	Percent	Percent
x-02 1	1520		12	.80	.89	.03				
2	1525		43	3.05	2.30	.15				
3	1526		23	1.16	.83	.18				
4	1527		46	2.84	4.50	.11				
5	1528		23	1.18	2.14	.38				
6	1529		25	.90	.44	.40				
7	1530		13	.29	.08	.45				
x-01 8	1531		12	.41	.46	.09				
9	1532		57	3.46	5.81	.06				
10	1533		25	1.92	1.30	.08				
11	1534		50	2.56	2.73	.20				
12	1535		11	.51	.46	.08				
13	1536		20	.87	1.07	.26				
14	1537		49	2.89	5.26	.06				
6-2 15	1538		42	2.51	3.68	.12				
16	1539		32	1.73	1.64	.17				
17	1540		78	4.28	8.13	.19				
18	1541		101	6.53	13.91	.08				
19	1542		77	4.26	8.17	.16				
20	1543		58	3.48	6.47	.08				

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.

[Signature]

Registered Assayer, Province of British Columbia



Kamloops Research & Assay Laboratory Ltd.

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS 2

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS, B.C. V1S 1A7
TELEPHONE 372-2784 TELEX 048-8320

CERTIFICATE OF ASSAY

TO Cyprus Anvil Mining Corporation

Certificate No. K-2704

Date May 1, 1980

I hereby certify that the following are the results of assays made by us upon the herein described drill core samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		Ounces Per Ton	Ounces Per Ton	Percent	Percent	Percent	Percent	Percent	Percent	Percent
21	1544		27	1.20	1.48	.27				
22	1545		11	.30	.51	.33				
23	1546		43	2.92	2.82	.19				
X-02 24	1547		64	3.62	8.40	.09				
25	1548		105	5.84	11.09	.22				
26	1549		10	.21	.40	.37				
27	1550		21	.52	.80	.51				
	<u>Repeats</u>									
	1520		11	.63	.89	.03				
	- 1525 X-01		41	2.89	2.30	.15				
	<u>Standards</u>									
	100		95	5.41	8.86	.11				
	200		82	4.94	6.64	.16				
	300		40	2.28	4.38	.04				
	MP-1		58	1.87	-	2.09				
	RU-1		11	-	2.28	.85				
	KC-1		1140	7.04	-	.11				

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.

Jas for Jas
Registered Assayer, Province of British Columbia



Kamloops Research & Assay Laboratory Ltd.

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS, B.C. V1S 1A7
TELEPHONE 372-2784 TELEX 048-8320

CERTIFICATE OF ASSAY

TO Cyprus Anvil Mining Corporation

Certificate No. K-2691

Date April 23, 1980

I hereby certify that the following are the results of assays made by us upon the herein described DY Core samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		Ounces Per Ton	g/tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent
21	1522		10	.77	1.34	.06				
22	1523		23	1.76	3.21	.05				
23	1524		26	2.19	3.65	.03				
24	3530		98	7.10	7.78	.06				
25	3531		60	3.77	3.28	.21				
26	3532		78	5.98	5.10	.18				
27	3533		16	.43	.48	.26				
28	3534		9	.33	.49	.13				
29	3535		18	1.20	.72	.29				
30	3536		61	5.15	8.57	.14				
31	3537		45	3.54	1.53	.72				
32	3538		63	4.72	9.43	.05				
33	3539		48	2.02	2.54	.52				
34	3540		28	.44	.46	.50				
35	3541		49	2.36	2.98	.09				
36	3542		59	2.93	5.21	.11				
37	3543		41	2.52	1.94	.24				
38	3544		40	2.95	2.74	.25				
39	3545		29	.93	.35	.26				
40	3546		19	.45	.18	.09				

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.


Registered Assayer, Province of British Columbia



Kamloops Research & Assay Laboratory Ltd.

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS, B.C. V1S 1A7
TELEPHONE 372-2784 TELEX 048-8320

CERTIFICATE OF ASSAY

TO Cyprus Anvil Mining Corporation

Certificate No. K-2691

Date April 23, 1980

I hereby certify that the following are the results of assays made by us upon the herein described DY Core samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		Ounces Per Ton	g/tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent
41	3547		20	.29	.12	.15				
42	3548		16	.47	.17	.25				
43	3549		40	2.48	1.34	.24				
01 44	3550		29	1.54	.93	.30				
	<u>Repeats</u>									
	1513 -02		22	1.27	3.32	.03				
	3532 -01		78	5.98	5.12	.18				
	3545 -01		29	.92	.34	.26				
	<u>Standards</u>									
1st Run	100		95	5.40	8.92	.11				
	200		82	4.86	6.62	.16				
	300		40	2.31	4.43	.04				
	RU-1		7	-	2.28	.85				
2nd Run	MP-1		58	1.80	15.8	-				
	100		95	5.33	8.90	.11				
	200		82	4.95	6.77	.16				
	300		40	2.31	4.42	.04				
	RU-1		7	-	2.28	.85				
	MP-1		58	1.85	16.0	2.09				

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.

cc Darryl Hanson


Registered Assayer, Province of British Columbia



Kamloops Research & Assay Laboratory Ltd.

**B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS**

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS, B.C. V1S 1A7
TELEPHONE 372-2784 TELEEX 048-8320

CERTIFICATE OF ASSAY

TO Cyprus Anvil Mining Corporation

330 - 355 Burrard

Vancouver, B.C. V6C 2G8

ATTENTION: Dr. G. Simpson

Certificate No. K-2678

Date April 17, 1980

I hereby certify that the following are the results of assays made by us upon the herein described drill samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		Ounces Per Ton	g/tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent
1	X 3521		29	2.15	1.37	.19				
2	X 3522		48	3.20	2.36	.44				
3	X 3523		41	2.94	2.62	.26				
4	X 3524		32	2.31	1.83	.20				
5	X 3524		25	1.38	1.95	.10				
6	X 3526		56	4.04	3.94	.26				
7	X 3527		46	2.92	2.28	.35				
8	X 3528		6	.56	.88	.06				
9	X 3529		29	2.29	1.68	.26				

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.

cc Mr. Darryl Hanson

Registered Assayer, Province of British Columbia

GEOCHEMICAL LOG

Kamloops Research and Assay Lab.

From	To	Int.	Samp. No.	Ag/AA GM/MT	Ag/Fa GM/MT	Pb %	Zn %	Pb+Zn %	S.G.	Cu %	BaO %	Au GMS/MT	Po %	Py %	Hg %	Mn %	Unit
710.6	710.9	0.3	3521	29.0		2.15	1.37	3.52		0.19							4H0
711.1	712.1	1.0	3522	48.0		3.20	2.36	5.56		0.44							4G4
712.1	713.3	1.2	3523	41.0		2.94	2.62	5.56		0.26							4G0
713.3	714.6	1.3	3524	32.0		2.31	1.83	4.14		0.20							4G0
714.6	717.0	2.4	3525	25.0		1.38	1.95	3.33		0.10							4A0
717.0	719.0	2.0	3526	56.0		4.04	3.94	7.98		0.26							4G8
719.0	721.2	2.2	3527	46.0		2.92	2.28	5.20		0.35							4G8
722.6	724.5	1.9	3528	6.0		0.56	0.88	1.44		0.06							4L7
724.5	724.8	0.3	3529	29.0		2.29	1.68	3.97		0.26							4E8
757.3	758.8	1.5	3530	98.0	102.0	7.10	7.78	14.88	4.46	0.06	28.9	1.10	1.4	13.6	.006		4G3
758.8	759.6	0.8	3531	60.0	50.0	3.77	3.28	7.05	4.39	0.21	6.2	1.37	6.3	26.4	.002		4K0
759.6	761.6	2.0	3532	78.0	76.0	5.98	5.12	11.10	4.18	0.18	9.2	1.10	13.3	15.6	.003		4K4
761.6	762.6	1.0	3533	16.0		0.43	0.48	0.91		0.26							4C0
762.6	764.2	1.6	3534	9.0		0.33	0.49	0.82		0.13							4A7
764.2	766.4	2.2	3535	18.0		1.20	0.72	1.92		0.29							4K0
766.4	766.8	0.4	3536	61.0	62.0	5.15	8.57	13.72	3.76	0.14	15.8	1.17	0.9	13.8	.005		4E4
766.8	767.8	1.0	3537	45.0	42.0	3.54	1.53	5.07	4.02	0.72	3.3	0.93	1.9	27.3	.002		4K0
767.8	768.3	0.5	3538	63.0	64.0	4.72	9.43	14.15	3.78	0.05	17.2	0.82	1.6	12.3	.006		4D6
768.3	769.4	1.1	3539	48.0		2.02	2.54	4.56		0.52							4E0
769.4	771.1	1.7	3540	28.0		0.44	0.46	0.90		0.50							4E0
798.4	799.3	0.9	3541	49.0		2.36	2.98	5.34		0.09							4K4
799.3	799.8	0.5	3542	59.0		2.93	5.21	8.14		0.11							4G4
799.8	801.4	1.6	3543	41.0		2.52	1.94	4.46		0.24							4K8
801.4	803.4	2.0	3544	40.0		2.95	2.74	5.69		0.25							4K8
803.4	805.0	1.6	3545	29.0		0.92	0.34	1.26		0.26							4K8
805.0	806.3	1.3	3546	19.0		0.45	0.18	0.63		0.09							4K6
806.3	807.7	1.4	3547	20.0		0.29	0.12	0.41		0.15							4K6
807.7	809.4	1.7	3548	16.0		0.47	0.17	0.64		0.25							4K8
809.4	811.1	1.7	3549	40.0		2.48	1.34	3.82		0.24							4K8
811.1	812.9	1.8	3550	20.0		1.54	0.93	2.47		0.30							4K8



Member
Canadian Testing
Association

KAMLOOPS RESEARCH & ASSAY LABORATORY LTD.

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS B.C.
V1S 1A7

PHONE: (604) 372-2784 — TELEX: 048-8320

CERTIFICATE OF ASSAY

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS
METALLURGISTS

1980 DY

TO Cyprus Anvil Mining Corporation
330 - 355 Burrard St.
Vancouver, B.C. V6C 2G8

Certificate No. K-3428

Date December 18, 1980

I hereby certify that the following are the results of assays made by us upon the herein described _____ samples

Kral No.	Marked	GOLD	SILVER	Py	Po	BaO	Hg	S.G.		
		grams per tonne	grams per tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent
1	X 1505	1.70	90	19.4	1.9	10.0	.006	4.51		
2	1506	1.17	106	13.0	1.1	26.5	.008	4.46		
3	1507	.82	108	15.6	2.3	22.3	.009	4.47		
4	1508	.27	40	2.6	1.2	2.3	.005	2.80		
5	1509	.34	38	2.4	.8	0.6	.005	2.72		
6	1540	1.51	82	19.7	.5	24.5	.007	4.27		
X-02 7	1541	1.37	98	23.7	1.5	1.7	.009	4.20		
8	1542	.75	78	18.5	3.0	27.2	.008	4.55		
9	1543	1.92	58	30.7	1.2	8.0	.010	4.58		
10	1547	.69	68	13.4	3.0	17.3	.005	3.88		
11	1548	1.70	100	17.1	3.3	3.1	.006	3.66		
12	1560	1.37	118	16.6	1.5	22.0	.005	5.21		
X-04 13	1561	2.09	19	34.7	7.8	.1	.002	4.57		
14	1562	1.37	113	9.3	.8	33.7	.009	4.42		
15	1651	1.23	63	15.2	2.5	9.3	.009	3.58		
16	1652	1.23	29	26.0	3.5	9.3	.005	4.36		
17	1653	.69	120	10.2	2.8	31.0	.010	4.44		
18	1654	.62	119	11.5	3.8	26.9	.009	4.65		
05 19	1655	.93	106	23.9	4.1	12.6	.007	4.85		
20	1656	.62	78	20.7	.9	21.9	.009	4.44		

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.

[Signature]
for R.B.B.

Registered Assayer, Province of British Columbia



Kamloops Research & Assay Laboratory Ltd.

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS, B.C. V1S 1A7
TELEPHONE 372-2784 TELEX 048-8320

CERTIFICATE OF ASSAY

TO Cyprus Anvil Mining Corporation

330 - 355 Burrard St.

Vancouver, B.C. V6C 2G8 Attention: Dr. G. Simpson

Certificate No. K-2716

Date May 8, 1980

I hereby certify that the following are the results of assays made by us upon the herein described drill core samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		Ounces Per Ton	g/tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent
Foxor 1 2	1551		20	2.38	.23	.35				
	1552		65	4.00	6.16	.17				

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.

cc Mr. Darryl Hanson

Registered Assayer, Province of British Columbia



Kamloops Research & Assay Laboratory Ltd.

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS, B.C. V1S 1A7
TELEPHONE 372-2784 TELEX 048-8320

CERTIFICATE OF ASSAY

TO Cyprus Anvil Mining Corporation

Certificate No. K-2704

330 - 355 Burrard St.

Date May 1, 1980

Vancouver, B.C. V6C 2G8

Attention: Dr. G. Simpson
cc Darryl Hanson

I hereby certify that the following are the results of assays made by us upon the herein described drill core samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		Ounces Per Ton	Ounces Per Ton	Percent	Percent	Percent	Percent	Percent	Percent	Percent
x-02 1	1520		12	.80	.89	.03				
2	1525		43	3.05	2.30	.15				
3	1526		23	1.16	.83	.18				
4	1527		46	2.84	4.50	.11				
5	1528		23	1.18	2.14	.38				
6	1529		25	.90	.44	.40				
7	1530		13	.29	.08	.45				
x-01 8	1531		12	.41	.46	.09				
9	1532		57	3.46	5.81	.06				
10	1533		25	1.92	1.30	.08				
11	1534		50	2.56	2.73	.20				
12	1535		11	.51	.46	.08				
13	1536		20	.87	1.07	.26				
14	1537		49	2.89	5.26	.06				
x-02 15	1538		42	2.51	3.68	.12				
16	1539		32	1.73	1.64	.17				
17	1540		78	4.28	8.13	.19				
18	1541		101	6.53	13.91	.08				
19	1542		77	4.26	8.17	.16				
20	1543		58	3.48	6.47	.08				

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.

Das for OesB

Registered Assayer, Province of British Columbia



Kamloops Research & Assay Laboratory Ltd.

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS 2

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS, B.C. V1S 1A7
TELEPHONE 372-2784 TELEX 048-8320

CERTIFICATE OF ASSAY

TO Cyprus Anvil Mining Corporation

Certificate No. K-2704

Date May 1, 1980

I hereby certify that the following are the results of assays made by us upon the herein described drill core samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		Ounces Per Ton	Ounces Per Ton	Percent	Percent	Percent	Percent	Percent	Percent	Percent
21	1544		27	1.20	1.48	.27				
22	1545		11	.30	.51	.33				
23	1546		43	2.92	2.82	.19				
X-02 24	1547		64	3.62	8.40	.09				
25	1548		105	5.84	11.09	.22				
26	1549		10	.21	.40	.37				
27	1550		21	.52	.80	.51				
	<u>Repeats</u>									
	1520		11	.63	.89	.03				
	1525		41	2.89	2.30	.15				
	<u>Standards</u>									
	100		95	5.41	8.86	.11				
	200		82	4.94	6.64	.16				
	300		40	2.28	4.38	.04				
	MP-1		58	1.87	-	2.09				
	RU-1		11	-	2.28	.85				
	KC-1		1140	7.04	-	.11				

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.

Jas for Jas

Registered Assayer, Province of British Columbia



Kamloops Research & Assay Laboratory Ltd.

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS, B.C. V1S 1A7
TELEPHONE 372-2784 TELEEX 048-8320

CERTIFICATE OF ASSAY

TO Cyprus Anvil Mining Corporation

330 - 355 Burrard St.

Vancouver, BC V6C 2G8 Attention: Dr. G. Simpson

Certificate No. K-2691

Date April 23, 1980

I hereby certify that the following are the results of assays made by us upon the herein described DY Core samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		Ounces Per Ton	g/tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent
1	1501		37	2.71	2.81	.11				
2	1502		5	.05	.77	.65				
3	1503		51	3.84	3.11	.24				
4	1504		24	2.02	1.93	.48				
5	1505		86	9.55	10.14	.26				
6	1506		104	8.82	10.24	.09				
7	1507		118	8.26	9.45	.08				
8	1508		42	2.50	5.66	.02				
9	1509		34	2.04	5.69	.02				
10	1510		23	1.44	2.76	.03				
11	1511		32	2.12	3.99	.03				
12	1512		27	2.04	2.98	.04				
13	1513		20	1.23	3.21	.03				
14	1514		32	2.00	4.80	.06				
15	1515		27	1.80	3.84	.06				
16	1516		23	1.49	3.22	.03				
17	1517		33	2.14	3.76	.03				
18	1518		13	.91	1.63	.05				
19	1519		10	.77	1.28	.02				
20	1521		9	.83	1.28	.04				

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.

Signature

Registered Assayer, Province of British Columbia



Kamloops Research & Assay Laboratory Ltd.

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS, B.C. V1S 1A7
TELEPHONE 372-2784 TELEX 048-8320

CERTIFICATE OF ASSAY

TO Cyprus Anvil Mining Corporation

Certificate No. K-2691

Date April 23, 1980

I hereby certify that the following are the results of assays made by us upon the herein described DY Core samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		Ounces Per Ton	g/tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent
21	1522		10	.77	1.34	.06				
22	1523		23	1.76	3.21	.05				
23	1524		26	2.19	3.65	.03				
24	3530		98	7.10	7.78	.06				
25	3531		60	3.77	3.28	.21				
26	3532		78	5.98	5.10	.18				
27	3533		16	.43	.48	.26				
28	3534		9	.33	.49	.13				
29	3535		18	1.20	.72	.29				
30	3536		61	5.15	8.57	.14				
31	3537		45	3.54	1.53	.72				
32	3538		63	4.72	9.43	.05				
33	3539		48	2.02	2.54	.52				
34	3540		28	.44	.46	.50				
35	3541		49	2.36	2.98	.09				
36	3542		59	2.93	5.21	.11				
37	3543		41	2.52	1.94	.24				
38	3544		40	2.95	2.74	.25				
39	3545		29	.93	.35	.26				
40	3546		19	.45	.18	.09				

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.


Registered Assayer, Province of British Columbia



Kamloops Research & Assay Laboratory Ltd.

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS, B.C. V1S 1A7
TELEPHONE 372-2784 TELEX 048-8320

CERTIFICATE OF ASSAY

TO Cyprus Anvil Mining Corporation

Certificate No. K-2691

Date April 23, 1980

I hereby certify that the following are the results of assays made by us upon the herein described DY Core samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		Ounces Per Ton	g/tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent
41	3547		20	.29	.12	.15				
42	3548		16	.47	.17	.25				
43	3549		40	2.48	1.34	.24				
01 44	3550		29	1.54	.93	.30				
	<u>Repeats</u>									
	1513 -02		22	1.27	3.32	.03				
	3532 -01		78	5.98	5.12	.18				
	3545 -01		29	.92	.34	.26				
	<u>Standards</u>									
1st Run	100		95	5.40	8.92	.11				
	200		82	4.86	6.62	.16				
	300		40	2.31	4.43	.04				
	RU-1		7	-	2.28	.85				
2nd Run	MP-1		58	1.80	15.8	-				
	100		95	5.33	8.90	.11				
	200		82	4.95	6.77	.16				
	300		40	2.31	4.42	.04				
	RU-1		7	-	2.28	.85				
	MP-1		58	1.85	16.0	2.09				

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.

cc Darryl Hanson

DAR J. Bess
Registered Assayer, Province of British Columbia

GEOCHEMICAL LOG

Kamloops Research and Assay Lab.

From	To	Int.	Samp. No.	Ag/AA GM/MT	Ag/Fa GM/MT	Pb %	Zn %	Pb+Zn %	S.G.	Cu %	BaO %	Au GMS/MT	Po %	Py %	Hg %	Mn %	Unit
731.9	733.3	1.4	1501	37.0		2.71	2.81	5.52		0.11							4H3
783.6	784.7	1.1	1502	5.0		0.05	0.77			0.65							4F0
827.8	829.5	1.7	1503	51.0		3.84	3.11	6.95		0.24							4E4
829.5	831.1	1.6	1504	24.0		2.02	1.98	4.00		0.48							4E4
831.1	833.0	1.9	1505	86.0	90.0	9.55	10.14	19.69	4.51	0.26	10.0	1.70	1.9	19.4	.006		4G4
833.0	835.0	2.0	1506	104.0	106.0	8.82	10.24	19.06	4.46	0.09	26.5	1.17	1.1	13.0	.008		4G4
835.0	837.2	2.2	1507	118.0	108.0	8.26	9.45	17.71	4.47	0.08	22.3	0.82	2.3	15.6	.009		4G4
837.2	839.0	1.8	1508	42.0	40.0	2.50	5.66	8.16	2.80	0.02	2.3	0.27	1.2	2.6	.005		4A4
839.0	841.0	2.0	1509	34.0	38.0	2.04	5.69	7.73	2.72	0.02	0.6	0.34	0.8	2.4	.005		4A4
841.0	843.0	2.0	1510	23.0		1.44	2.76	4.20		0.03							4A4
843.0	845.0	2.0	1511	32.0		2.12	3.99	6.11		0.03							4A4
845.0	847.0	2.0	1512	27.0		2.04	2.98	5.02		0.04							4A4
847.0	848.2	1.2	1513	22.0		1.27	3.32	4.59		0.03							4A4
848.2	850.3	2.1	1514	32.0		2.00	4.80	6.80		0.06							4A4
850.3	852.1	1.8	1515	27.0		1.80	3.84	5.64		0.06							4A4
852.1	854.3	2.2	1516	23.0		1.49	3.22	4.71		0.03							4A4
854.3	855.9	1.6	1517	33.0		2.14	3.76	5.90		0.03							4A4
855.9	857.9	2.0	1518	13.0		0.91	1.63	2.54		0.05							4A0
857.9	959.9	2.0	1519	10.0		0.77	1.28	2.05		0.02							4A0
859.9	862.0	2.1	1520	11.0		0.63	0.89	1.52		0.03							4A0
862.0	862.8	0.8	1521	9.0		0.83	1.28	2.11		0.04							4A0
862.8	864.8	2.0	1522	10.0		0.77	1.34	2.11		0.06							4A4
864.8	866.8	2.0	1523	23.0		1.76	3.21	4.97		0.05							4A4
866.8	868.7	1.9	1524	26.0		2.19	3.65	5.84		0.03							4A4
872.7	874.0	1.3	1552	65.0		4.00	6.16	10.16		0.17							4G0
876.8	879.2	2.4	1534	50.0		2.56	2.73	5.29		0.20							4A4
880.1	882.3	2.2	1535	11.0		0.51	0.46	0.97		0.08							4A0
883.1	883.5	0.4	1536	20.0		0.87	1.07	1.94		0.26							4A4



Member
Canadian Testing
Association

KAMLOOPS RESEARCH & ASSAY LABORATORY LTD.

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS B.C.
V1S 1A7

PHONE: (604) 372-2784 — TELEX: 048-8320

CERTIFICATE OF ASSAY

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS
METALLURGISTS

TO Cyprus Anvil Mining Corporation

330 - 355 Burrard St.

Vancouver, B.C. V2C 2G8 Attention: Dr. G. Simpson

Certificate No. K-2775

Date May 28, 1980

I hereby certify that the following are the results of assays made by us upon the herein described drill core samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		Ounces Per Ton	g/tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent
1	1553		45	2.38	3.44	.17				
2	1554		20	.98	.50	.49				
3	1555		46	3.75	2.72	.05				
4	1556		37	1.85	2.76	.32				
5	1557		24	1.52	1.46	.07				
6	1558		52	.90	.97	.14				
7	1560		135	7.38	9.30	.20				
8	1561		16	.56	.49	.43				
9	1562		127	7.19	9.52	.05				
10	1563		1	.04	.04	.12				
11	1564		1	.17	.09	.14				
12	1565		1	.39	.24	.10				
13	1566		1	.03	.04	.07				
14	1567		1	.02	.02	.04				
15	1568		1	.02	.02	.06				
16	1569		5	.22	.08	.10				
17	1570		10	.72	.94	.05				
18	1571		36	1.39	1.32	.15				
19	1572		40	2.75	1.92	.31				
20	1573		43	2.72	3.95	.04				

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.

WAB for PLS

Registered Assayer, Province of British Columbia

GEOCHEMICAL LOG

Kamloops Research and Assay Lab.

<u>From</u>	<u>To</u>	<u>Int.</u>	<u>Samp.</u> <u>No.</u>	<u>Ag/AA</u> <u>GM/MT</u>	<u>Ag/Fa</u> <u>GM/MT</u>	<u>Pb %</u>	<u>Zn %</u>	<u>Pb+Zn</u> <u>%</u>	<u>S.G.</u>	<u>Cu %</u>	<u>BaO %</u>	<u>Au</u> <u>GMS/MT</u>	<u>Po %</u>	<u>Py %</u>	<u>Hg %</u>	<u>Mn %</u>	<u>Unit</u>
543.0	543.8	0.8	1553	45.0		2.38	3.44	5.82		0.17							4E0



KAMLOOPS RESEARCH & ASSAY LABORATORY LTD.

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS B.C.
V1S 1A7

PHONE: (604) 372-2784 — TELEX: 048-8320

CERTIFICATE OF ASSAY

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS
METALLURGISTS

1980 D1

TO Cyprus Anvil Mining Corporation
330 - 355 Burrard St.
Vancouver, B.C. V6C 2G8

Certificate No. K-3428

Date December 18, 1980

I hereby certify that the following are the results of assays made by us upon the herein described _____ samples

Kral No.	Marked	GOLD	SILVER	Py	Po	BaO	Hg	S.G.		
		grams per tonne	grams per tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent
1	X 1505	1.70	90	19.4	1.9	10.0	.006	4.51		
2	1506	1.17	106	13.0	1.1	26.5	.008	4.46		
3	1507	.82	108	15.6	2.3	22.3	.009	4.47		
4	1508	.27	40	2.6	1.2	2.3	.005	2.80		
5	1509	.34	38	2.4	.8	0.6	.005	2.72		
6	1540	1.51	82	19.7	.5	24.5	.007	4.27		
X-02 7	1541	1.37	98	23.7	1.5	1.7	.009	4.20		
8	1542	.75	78	18.5	3.0	27.2	.008	4.55		
9	1543	1.92	58	30.7	1.2	8.0	.010	4.58		
10	1547	.69	68	13.4	3.0	17.3	.005	3.88		
11	1548	1.70	100	17.1	3.3	3.1	.006	3.66		
12	1560	1.37	118	16.6	1.5	22.0	.005	5.21		
X-04 13	1561	2.09	19	34.7	7.8	.1	.002	4.57		
14	1562	1.37	113	9.3	.8	33.7	.009	4.42		
15	1651	1.23	63	15.2	2.5	9.3	.009	3.58		
16	1652	1.23	29	26.0	3.5	9.3	.005	4.36		
17	1653	.69	120	10.2	2.8	31.0	.010	4.44		
18	1654	.62	119	11.5	3.8	26.9	.009	4.65		
05 19	1655	.93	106	23.9	4.1	12.6	.007	4.85		
20	1656	.62	78	20.7	.9	21.9	.009	4.44		

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.

[Signature]

Registered Assayer, Province of British Columbia



KAMLOOPS RESEARCH & ASSAY LABORATORY LTD.

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS B.C.
V1S 1A7

PHONE: (604) 372-2784 — TELEX: 048-8320

CERTIFICATE OF ASSAY

CALCULATION ERROR ON ORIGINAL SHEET

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS
METALLURGISTS

X-04

TO Cyprus Anvil Mining Corporation
330 - 355 Burrard Street
Vancouver, B.C. V6C 2G8

Certificate No. K-2775

Date December 9, 1980

I hereby certify that the following are the results of assays made by us upon the herein described _____ samples

Kral No.	Marked	GOLD	SILVER							
		Ounces Per Ton	g/tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent
	1560 1562		112 106							

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.

Registered Assayer, Province of British Columbia



Member
Canadian Testing
Association

KAMLOOPS RESEARCH & ASSAY LABORATORY LTD.

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS B.C.
V1S 1A7

PHONE: (604) 372-2784 — TELEX: 048-8320

CERTIFICATE OF ASSAY

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS
METALLURGISTS

TO Cyprus Anvil Mining Corporation

330 - 355 Burrard St.

Vancouver, B.C. V2C 2G8 Attention: Dr. G. Simpson

Certificate No. K-2775

Date May 28, 1980

I hereby certify that the following are the results of assays made by us upon the herein described drill core samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		Ounces Per Ton	g/tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent
1	1553		45	2.38	3.44	.17				
2	1554		20	.98	.50	.49				
3	1555		46	3.75	2.72	.05				
4	1556		37	1.85	2.76	.32				
5	1557		24	1.52	1.46	.07				
Xo4 6	1559		52	.90	.97	.14				
7	1560		135	7.38	9.30	.20				
8	1561		16	.56	.49	.43				
9	1562		127	7.19	9.52	.05				
10	1563		1	.04	.04	.12				
11	1564		1	.17	.09	.14				
12	1565		1	.39	.24	.10				
13	1566		1	.03	.04	.07				
14	1567		1	.02	.02	.04				
15	1568		1	.02	.02	.06				
16	1569		5	.22	.08	.10				
17	1570		10	.72	.94	.05				
18	1571		36	1.39	1.32	.15				
19	1572		40	2.75	1.92	.31				
20	1573		43	2.72	3.95	.04				

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.

JAB for PERS

Registered Assayer, Province of British Columbia



Member
Canadian Testing
Association

KAMLOOPS RESEARCH & ASSAY LABORATORY LTD.

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS B.C.
V1S 1A7

PHONE: (604) 372-2784 — TELEX: 048-8320

CERTIFICATE OF ASSAY

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS
METALLURGISTS 2

TO Cyprus Anvil Mining Corporation

Certificate No. K-2775

Date May 28, 1980

I hereby certify that the following are the results of assays made by us upon the herein described drill core samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		Ounces Per Ton	g/tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent
21	1574		78	6.04	6.35	.06				
22	1575		8	.50	1.29	.12				
23	1576		7	.27	.41	.26				
24	1577		22	1.49	1.33	.16				
25	1578		14	1.09	.98	.14				
	<u>Repeats</u>									
	1557		24	1.46	1.45	.07				
	1568		1	.02	.02	.06				
	<u>Standards</u>									
	100		95	5.43	8.73	.11				
	200		82	4.89	6.59	.15				
	300		40	2.29	4.37	.04				
	MP-1		58	1.88	15.75	2.08				
	RU-1		7	-	2.17	.85				

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.

cc. Mr. Darryl Hanson

Darryl Hanson

Registered Assayer, Province of British Columbia

80-X-05



Member
Canadian Testing
Association

KAMLOOPS RESEARCH & ASSAY LABORATORY LTD.

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS B.C.
V1S 1A7

PHONE: (604) 372-2784 — TELEX: 048-8320

CERTIFICATE OF ASSAY

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS
METALLURGISTS

1980 D1

TO Cyprus Anvil Mining Corporation

330 - 355 Burrard St.

Vancouver, B.C. V6C 2G8

Certificate No. K-3428

Date December 18, 1980

I hereby certify that the following are the results of assays made by us upon the herein described _____ samples

Kral No.	Marked	GOLD	SILVER	Py	Po	BaO	Hg	S.G.		
		grams per tonne	grams per tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent
1	X 1505	1.70	90	19.4	1.9	10.0	.006	4.51		
2	1506	1.17	106	13.0	1.1	26.5	.008	4.46		
3	1507	.82	108	15.6	2.3	22.3	.009	4.47		
4	1508	.27	40	2.6	1.2	2.3	.005	2.80		
5	1509	.34	38	2.4	.8	0.6	.005	2.72		
6	1540	1.51	82	19.7	.5	24.5	.007	4.27		
X-02 7	1541	1.37	98	23.7	1.5	1.7	.009	4.20		
8	1542	.75	78	18.5	3.0	27.2	.008	4.55		
9	1543	1.92	58	30.7	1.2	8.0	.010	4.58		
10	1547	.69	68	13.4	3.0	17.3	.005	3.88		
11	1548	1.70	100	17.1	3.3	3.1	.006	3.66		
12	1560	1.37	118	16.6	1.5	22.0	.005	5.21		
X-04 13	1561	2.09	19	34.7	7.8	.1	.002	4.57		
14	1562	1.37	113	9.3	.8	33.7	.009	4.42		
15	1651	1.23	63	15.2	2.5	9.3	.009	3.58		
16	1652	1.23	29	26.0	3.5	9.3	.005	4.36		
17	1653	.69	120	10.2	2.8	31.0	.010	4.44		
18	1654	.62	119	11.5	3.8	26.9	.009	4.65		
05 19	1655	.93	106	23.9	4.1	12.6	.007	4.85		
20	1656	.62	78	20.7	.9	21.9	.009	4.44		

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.

Registered Assayer, Province of British Columbia



KAMLOOPS RESEARCH & ASSAY LABORATORY LTD.

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS B.C.
V1S 1A7

PHONE: (604) 372-2784 — TELEX: 048-8320

CERTIFICATE OF ASSAY

**B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS
METALLURGISTS**

TO Cyprus Anvil Mining Corporation

330 - 355 Burrard St.

Vancouver, B.C. V6C 2G8 Attention: Dr. G. Simpson

Certificate No. K-2846

Date June 19, 1980

705

I hereby certify that the following are the results of assays made by us upon the herein described drill core samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		Ounces Per Ton	g/tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent
1	1651		83	4.03	6.09	.10				
2	1652		33	1.83	3.26	.13				
3	1653		125	7.17	10.34	.08				
4	1654		113	8.50	9.55	.08				
5	1655		103	8.51	5.92	.07				
6	1656		74	5.22	9.59	.08				
7	1657		99	7.55	8.25	.12				
8	1658		66	5.41	7.84	.18				
9	1659		74	5.31	8.51	.11				
	<u>Repeat</u>									
	1655		104	8.58	5.96	.07				
	<u>Standards</u>									
	100		84	5.57	8.92	.11				
	200		84	4.99	6.70	.16				
	300		40	2.28	4.41	.05				
	MP-1		57	1.92	15.9	-				
	RU-1		10	-	2.42	-				
	KC-1		-	6.82	-	.11				

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.

cc Mr. Darryl Hanson

[Handwritten Signature]

Registered Assayer, Province of British Columbia

GEOCHEMICAL LOG

Kamloops Research and Assay Lab.

From	To	Int.	Samp. No.	Ag/AA GM/MT	Ag/Fa GM/MT	Pb %	Zn %	Pb+Zn %	S.G.	Cu %	BaO %	Au GMS/MT	Po %	Py %	Hg %	Mn %	Unit
744.9	746.2	1.3	1660	60.0		3.93	3.80	7.73		0.18							4G0
755.3	757.3	2.0	1661	2.0		0.18	0.29			0.20							4L2
757.3	759.3	2.0	1662	11.0		0.05	0.15			0.02							4L2
759.3	760.2	0.9	1663	2.0		0.04	0.05			0.09							4L2
846.5	847.8	1.3	1651	83.0	63.0	4.03	6.09	10.12	3.58	0.10	9.3	1.23	2.5	15.2	.009		4J4
847.8	849.1	1.3	1652	33.0	29.0	1.83	3.26	5.09	4.36	0.13	9.3	1.23	3.5	26.0	.005		4E4
849.1	851.1	2.0	1653	125.0	120.0	7.17	10.34	17.51	4.44	0.08	31.0	0.69	2.8	10.2	.010		4G4
851.1	853.2	2.1	1654	113.0	119.0	8.50	9.55	18.05	4.65	0.08	26.9	0.62	3.8	11.5	.009		4G4
853.2	854.8	1.6	1655	103.0	106.0	8.51	5.92	14.43	4.85	0.07	12.6	0.93	4.1	23.9	.007		4E6
854.8	856.1	1.3	1656	74.0	78.0	5.22	9.59	14.81	4.44	0.08	21.9	0.62	0.9	20.7	.009		4E4
856.1	857.4	1.3	1657	99.0	102.0	7.55	8.25	15.80	4.49	0.12	19.1	1.17	1.7	19.4	.007		4G4
857.4	859.4	2.0	1658	66.0	85.0	5.41	7.84	13.25	4.53	0.18	34.8	1.10	0.6	12.4	.007		4G0
859.4	861.2	1.8	1659	74.0	87.0	5.31	8.51	13.82	4.68	0.11	29.2	0.82	1.0	15.2	.009		4G4
886.9	888.4	1.5	1664	66.0		3.61	6.17	9.78		0.04							4A4
893.1	895.5	2.4	1665	5.0		0.83	2.03	2.86		0.03							4L4
895.5	896.1	0.6	1666	16.0		1.51	4.26	5.77		0.06							4A0
896.1	898.1	2.0	1667	58.0	66.0	3.71	6.72	10.43	4.36	0.20	12.1	2.16	1.8	24.0	.007		4E0
898.1	900.0	1.9	1668	51.0	54.0	3.77	3.43	7.20	4.42	0.12	1.5	1.30	7.8	30.3	.005		4E0
900.0	901.1	1.1	1669	64.0	59.0	3.93	5.00	8.93	4.15	0.10	1.9	1.23	2.6	27.8	.005		4C0
901.4	903.4	2.0	1670	5.0		0.45	0.61	1.06		0.04							4E1
903.4	904.9	1.5	1671	5.0		0.16	0.45	0.61		0.38							4E1
904.9	905.5	0.6	1672	12.0		0.91	1.73	2.64		0.19							4C8
905.5	907.5	2.0	1673	21.0		0.94	1.57	2.51		0.60							4E8
907.5	909.2	1.7	1674	24.0		0.48	0.68	1.16		0.85							4C7
943.3	944.0	0.7	1675	20.0		1.90	3.16	5.06		0.09							4A0
944.0	944.4	0.4	1676	79.0		6.15	8.39	14.54		0.09							4E0
944.4	946.4	2.0	1677	20.0		1.57	2.42	3.99		0.09							4A0
946.4	947.8	1.4	1678	14.0		1.45	0.96	2.41		0.23							4A0



Member
Canadian Testing
Association

KAMILOOPS RESEARCH & ASSAY LABORATORY LTD.

2095 WEST TRANS CANADA HIGHWAY — KAMILOOPS B.C.
V1S 1A7

PHONE: (604) 372-2784 — TELEX: 048-8320

CERTIFICATE OF ASSAY

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS
METALLURGISTS 2

TO Cyprus Anvil Mining Corporation

Certificate No. K-3428

Date December 18, 1980

I hereby certify that the following are the results of assays made by us upon the herein described samples

Kral No.	Marked	GOLD	SILVER	Py	Po	BaO	Hg	S.G.		
		grams per tonne	grams per tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent
21	X 1657	1.17	102	19.4	1.7	19.1	.007	4.49		
22	1658	1.10	85	12.4	.6	34.8	.007	4.53		
23	1659	.82	87	15.2	1.0	29.2	.009	4.68		
24	1667	2.16	66	24.0	1.8	12.1	.007	4.36		
25	1668	1.30	54	30.3	7.8	1.5	.005	4.42		
26	1669	1.23	59	27.8	2.6	1.9	.005	4.15		
27	1693	.55	59	16.3	4.3	22.0	.004	4.19		
28	1694	.62	64	20.5	2.6	21.9	.004	4.86		
29	1701	1.47	89	18.2	2.8	13.3	.006	4.35		
30	1702	1.71	45	28.7	11.8	1.9	.003	4.83		
31	1703	1.09	84	15.2	2.3	28.2	.007	4.55		
32	1711	1.65	116	17.2	17.2	0.08	.005	4.46		
33	1712	1.78	50	25.8	12.9	0.06	.003	4.42		
34	1713	1.17	99	16.9	9.4	10.7	.005	3.94		
35	1722	.69	32	15.8	7.8	5.3	.006	4.12		
36	1723	.82	35	16.5	11.3	0.9	.003	3.69		
37	1744	.82	84	19.4	3.1	16.8	.005	4.38		
38	1749	.62	53	13.5	1.5	0.17	.004	3.30		
39	1750	.69	33	30.9	.8	3.1	.007	4.58		
40	1751	.75	50	16.6	5.1	26.6	.005	4.46		

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.

[Signature]
R.G.B.

Registered Assayer, Province of British Columbia

GEOCHEMICAL LOG

Kamloops Research and Assay Lab.

<u>From</u>	<u>To</u>	<u>Int.</u>	<u>Samp.</u> <u>No.</u>	<u>Ag/AA</u> <u>GM/MT</u>	<u>Ag/Fa</u> <u>GM/MT</u>	<u>Pb %</u>	<u>Zn %</u>	<u>Pb+Zn</u> <u>%</u>	<u>S.G.</u>	<u>Cu %</u>	<u>BaO %</u>	<u>Au</u> <u>GMS/MT</u>	<u>Po %</u>	<u>Py %</u>	<u>Hg %</u>	<u>Mn %</u>	<u>Rec.</u>	<u>Unit</u>
842.0	842.5	0.5	1690	6.0		0.35	0.23	0.58		0.44							0.5	4H9
842.5	844.5	2.0	1682	42.0		2.93	2.84	5.77		0.27							2.0	4G8
844.5	846.5	2.0	1683	7.0		4.61	5.45	10.06		0.24							2.0	4G8
846.5	848.7	2.2	1684	66.0		4.71	4.63	9.34		0.33							2.2	4G8
848.7	850.6	1.9	1685	24.0		1.63	1.45	3.08		0.07							1.9	4A0
852.5	854.5	2.0	1686	2.0		0.01	0.01			0.01							2.0	4L7
854.5	856.5	2.0	1687	1.0		0.01	0.01			0.01							2.0	4L7
856.5	858.5	2.0	1688	3.0		0.15	0.12			0.03							1.9	4L7
858.5	860.5	2.0	1689	2.0		0.08	0.86			0.03							2.0	4L7
860.5	861.9	1.4	1691	11.0		0.04	0.06			0.01							1.4	4L7
861.9	862.7	0.8	1692	2.0		0.22	0.41			0.04							0.8	4L3
862.7	863.2	0.5	1693	59.0	59.0	4.14	6.11	10.25	4.19	0.05	22.0	0.55	4.3	16.3	.004		0.4	4D4
863.2	863.7	0.5	1694	63.0	64.0	4.75	6.65	11.40	4.86	0.09	21.9	0.62	2.6	20.5	.004		0.5	4G4
863.7	864.7	1.0	1695	4.0		0.47	0.50	0.97		0.11							1.0	4A0
864.7	867.0	2.3	1696	41.0		2.96	2.51	5.47		0.30							2.3	4E4
867.0	868.0	1.0	1697	57.0		2.94	3.20	6.14		0.23							1.0	4E8
868.0	868.5	0.5	1698	6.0		0.60	0.80	1.40		0.06							0.4	4L0
868.5	870.2	1.7	1699	51.0		2.61	2.73	5.34		0.48							1.7	4E0
870.2	870.5	0.3	1700	55.0		3.32	0.25 *	3.57		0.24							0.3	4H0
875.0	875.4	0.4	1701	84.0	89.0	6.38	8.13	14.51	4.35	0.14	13.3	1.47	2.8	18.2	.006		0.4	4G4
875.4	876.1	0.7	1702	47.0	45.0	3.01	2.13	5.14	4.83	0.48	1.9	1.71	11.8	28.7	.003		0.7	4E8
876.1	877.1	1.0	1703	79.0	84.0	5.83	8.13	13.96	4.55	0.12	28.2	1.09	2.3	15.2	.007		1.0	4G4
877.1	877.5	0.4	1704	23.0		0.70	0.44	1.14		0.45							0.4	4E8
877.5	878.4	0.9	1705	11.0		0.76	1.20	1.96		0.15							0.9	4C0
878.4	879.9	1.5	1706	21.0		1.15	1.05	2.20		0.34							1.4	4A0
879.9	881.3	1.4	1707	23.0		1.65	2.17	3.82		0.44							1.4	4D7
881.3	881.7	0.4	1708	36.0		2.38	4.15	6.53		0.11							0.4	4G0
881.7	882.3	0.6	1709	8.0		0.61	1.25	1.86		0.33							0.6	4D7
882.3	883.2	0.9	1710	19.0		1.36	2.02	3.38		0.24							0.9	4E1
883.2	885.4	2.2	1711	127.0	116.0	0.96	5.43	6.39	4.46	0.15	0.08	1.65	17.2	17.2	.005		2.2	4D8
885.4	886.1	0.7	1712	52.0	50.0	4.22	2.00	6.22	4.42	0.20	0.06	1.78	12.9	25.8	.003		0.7	4E8
886.1	888.6	2.5	1713	105.0	99.0	7.20	6.46	13.66	3.94	0.20	10.7	1.17	9.4	16.9	.005		2.5	4G4

GEOCHEMICAL LOG

Kamloops Research and Assay Lab.

<u>From</u>	<u>To</u>	<u>Int.</u>	<u>Samp.</u> <u>No.</u>	<u>Ag/AA</u> <u>GM/MT</u>	<u>Ag/Fa</u> <u>GM/MT</u>	<u>Pb %</u>	<u>Zn %</u>	<u>Pb+Zn</u> <u>%</u>	<u>S.G.</u>	<u>Cu %</u>	<u>BaO %</u>	<u>Au</u> <u>GMS/MT</u>	<u>Po %</u>	<u>Py %</u>	<u>Hg %</u>	<u>Mn %</u>	<u>Rec.</u>	<u>Unit</u>
743.0	743.5	0.5	5145	77.0		5.50	7.96	13.46		0.07							0.5	4G4
743.5	743.8	0.3	5146	56.0		4.36	5.24	9.60		0.04							0.3	4E0
746.5	747.2	0.7	5147	116.0	115.0	7.15	10.20	17.35	3.92	0.13	14.6	0.62	2.6	12.8	.004		0.7	4G4
747.2	748.5	1.3	5148	22.0	20.0	1.73	2.37	4.10	2.79	0.04	2.1	0.30	3.8	4.0	.001		1.3	4A4
748.5	749.6	1.1	5149	71.0	65.0	4.87	6.64	11.51	4.45	0.14	13.8	0.96	3.6	20.4	.004		1.1	4G4
749.6	751.1	1.5	5150	40.0	36.0	2.42	1.92	4.34	4.22	0.28	0.1	2.54	8.5	30.5	.001		1.5	4E4
751.1	753.4	2.3	1744	84.0	84.0	5.72	6.26	11.98	4.38	0.11	16.8	0.82	3.1	19.4	.005		2.1	4G4
801.6	803.6	2.0	1745	3.0		0.08	0.12			0.06							1.9	4L6
803.6	805.6	2.0	1746	2.0		0.02	0.03			0.07							1.8	4L6
805.6	807.5	1.9	1747	2.0		0.09	0.15			0.05							1.9	4L6
810.0	810.9	0.9	1748	35.0		2.17	3.61	5.78		0.12							0.9	4A0
810.9	811.2	0.3	1749	62.0	53.0	3.85	9.02	12.87	3.30	0.01	0.17	0.62	1.5	13.5	.004		0.3	4A4
811.2	811.7	0.5	1750	38.0	33.0	3.07	11.10	14.17	4.58	0.03	3.1	0.69	0.8	30.9	.007		0.5	4E6
811.7	813.2	1.5	1751	51.0	50.0	4.12	4.89	9.01	4.46	0.12	26.6	0.75	5.1	16.6	.005			4G0
813.2	814.4	1.2	1752	56.0	52.0	3.67	5.23	8.90	4.13	0.18	17.5	0.96	4.9	16.1	.004			4G0
814.4	815.0	0.6	1753	58.0	51.0	3.42	5.50	8.92	3.78	0.03	0.9	0.75	1.0	24.0	.004			4C0
815.0	816.1	1.1	1754	41.0	38.0	2.48	2.56	5.04	3.22	0.12	0.2	0.69	1.5	10.0	.003			4A4
816.1	818.8	2.7	1755	11.0		0.61	0.36	0.97		0.18							2.6	4A0
818.8	820.5	1.7	1756	57.0		3.91	1.81	5.72		0.21							1.6	4A4
825.2	827.2	2.0	1761	31.0		1.97	3.43	5.40		0.07							1.9	4A0
827.2	828.0	0.8	1762	3.0		0.03	0.03			0.02							0.8	4A0
832.7	834.7	2.0	1757	2.0		0.06	0.06			0.06							2.0	4L6
834.7	836.7	2.0	1758	5.0		0.09	0.08			0.06							2.0	4L6
836.7	838.7	2.0	1759														2.0	4L6
850.7	851.2	0.5	1760	37.0		1.84	2.12	3.96		0.28							0.4	4D4



Member
Canadian Testing
Association

KAMLOOPS RESEARCH & ASSAY LABORATORY LTD.

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS B.C.
V1S 1A7

PHONE: (604) 372-2784 — TELEX: 048-8320

CERTIFICATE OF ASSAY

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS
METALLURGISTS 2

TO Cyprus Anvil Mining Corporation

Certificate No. K-3428

Date December 18, 1980

I hereby certify that the following are the results of assays made by us upon the herein described _____ samples

Kral No.	Marked	GOLD	SILVER	Py	Po	BaO	Hg	S.G.		
		grams per tonne	grams per tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent
21	X 1657	1.17	102	19.4	1.7	19.1	.007	4.49		
22	1658	1.10	85	12.4	.6	34.8	.007	4.53		
23	1659	.82	87	15.2	1.0	29.2	.009	4.68		
24	1667	2.16	66	24.0	1.8	12.1	.007	4.36		
25	1668	1.30	54	30.3	7.8	1.5	.005	4.42		
26	1669	1.23	59	27.8	2.6	1.9	.005	4.15		
27	1693	.55	59	16.3	4.3	22.0	.004	4.19		
28	1694	.62	64	20.5	2.6	21.9	.004	4.86		
29	1701	1.47	89	18.2	2.8	13.3	.006	4.35		
30	1702	1.71	45	28.7	11.8	1.9	.003	4.83		
31	1703	1.09	84	15.2	2.3	28.2	.007	4.55		
32	1711	1.65	116	17.2	17.2	0.08	.005	4.46		
33	1712	1.78	50	25.8	12.9	0.06	.003	4.42		
34	1713	1.17	99	16.9	9.4	10.7	.005	3.94		
35	1722	.69	32	15.8	7.8	5.3	.006	4.12		
36	1723	.82	35	16.5	11.3	0.9	.003	3.69		
37	1744	.82	84	19.4	3.1	16.8	.005	4.38		
38	1749	.62	53	13.5	1.5	0.17	.004	3.30		
39	1750	.69	33	30.9	.8	3.1	.007	4.58		
40	1751	.75	50	16.6	5.1	26.6	.005	4.46		

05

06

(107)

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.

Registered Assayer, Province of British Columbia



Member
Canadian Testing
Association

KAMLOOPS RESEARCH & ASSAY LABORATORY LTD.

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS B.C.
V1S 1A7

PHONE: (604) 372-2784 — TELEX: 048-8320

CERTIFICATE OF ASSAY

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS
METALLURGISTS 3

TO Cyprus Anvil Mining Corporation


Certificate No. K-3428

Date December 18, 1980

I hereby certify that the following are the results of assays made by us upon the herein described _____ samples

Kral No.	Marked	GOLD	SILVER	Py	Po	BaO	Hg	S.G.		
		grams per tonne	grams per tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent
41	X 1752	.96	52	16.1	4.9	17.5	.004	4.13		
42	1753	.75	51	24.0	1.0	0.9	.004	3.78		
43	1754	.69	38	10.0	1.5	0.2	.003	3.22 >	*
44	1766	1.51	75	24.1	1.6	14.3	.006	3.90		
45	1767	.69	64	18.7	1.8	14.8	.006	4.43		
46	1768	.93	83	24.2	1.7	6.5	.006	4.29		
47	1769	.75	9	16.2	4.3	0.7	.002	3.10		
48	1770	1.17	108	16.2	1.4	24.4	.007	4.35		
49	1771	.82	106	17.0	4.2	20.9	.006	4.54		
50	1772	1.47	24	34.4	9.5	0.1	.003	4.28		
51	1773	.75	17	17.5	7.3	1.3	.002	3.62		
52	1774	.99	90	18.8	1.5	11.0	.008	4.23		
53	1775	2.84	140	31.7	.6	6.5	.007	5.10		
54	1776	1.37	73	36.0	.4	0.4	.006	4.63		
55	1777	.55	99	11.5	1.1	31.6	.007	4.51		
56	1778	.75	138	10.8	2.1	25.6	.008	4.75		
57	1779	1.16	77	21.6	1.0	13.3	.007	4.27		
58	1785	.69	109	15.7	1.4	22.2	.007	4.45		
59	1786	1.71	51	28.2	6.5	2.0	.004	4.50		
60	1787	.69	83	14.8	6.4	15.7	.004	4.25		

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.


Registered Assayer, Province of British Columbia



KAMLOOPS RESEARCH & ASSAY LABORATORY LTD.

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS B.C.
V1S 1A7

PHONE: (604) 372-2784 — TELEX: 048-8320

CERTIFICATE OF ASSAY

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS
METALLURGISTS 6

TO Cyprus Anvil Mining Corporation


Certificate No. K-3428

Date December 19, 1980

I hereby certify that the following are the results of assays made by us upon the herein described _____ samples

Kral No.	Marked	GOLD	SILVER	Py	Po	BaO	Hg	S.G.		
		grams per tonne	grams per tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent
101	X 3530	1.10	102	13.6	1.4	28.9	.006	4.46		
102	3531	1.37	50	26.4	6.3	6.2	.002	4.39		
103	3532	1.10	76	15.6	13.3	9.2	.003	4.18		
01 104	3536	1.17	62	13.8	.9	15.8	.005	3.76		
105	3537	.93	42	27.3	1.9	3.3	.002	4.02		
106	3538	.82	64	12.3	1.6	17.2	.006	3.78		
107	5147	.62	115	12.8	2.6	14.6	.004	3.92		
108	5148	.30	20	4.0	3.8	2.1	.001	2.79		
109	5149	.96	65	20.4	3.6	13.8	.004	4.45		
07 110	X 5150	2.54	36	30.5	8.5	0.1	.001	4.22		

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.


Registered Assayer, Province of British Columbia



Member
Canadian Testing
Association

KAMLOOPS RESEARCH & ASSAY LABORATORY LTD.

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS B.C.
V1S 1A7

PHONE: (604) 372-2784 — TELEX: 048-8320

CERTIFICATE OF ASSAY

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS
METALLURGISTS

TO Cyprus Anvil Mining Corporation

330 - 355 Burrard St.

Vancouver, B.C. V6C 2G8

(F)
X-07

Certificate No. K-3030

Date August 6, 1980

I hereby certify that the following are the results of assays made by us upon the herein described DY core samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		Ounces Per Ton	g/tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent
1	1745 X		3	.08	.12	.06				
2	1746 X		2	.02	.03	.07				
3	1747 X		2	.09	.15	.05				
4	1748 X		35	2.17	3.61	.12				
5	1749 X		62	3.85	9.02	.01				
6	1750 X		38	3.07	11.10	.03				
7	1751 X		51	4.12	4.89	.12				
8	1752 X		56	3.67	5.23	.18				
9	1753 X		58	3.42	5.50	.03				
10	1754 X		41	2.47	2.54	.13				
11	1755 X		11	.61	.36	.18				
12	1756 X		57	3.91	1.81	.21				
13	1757 X		2	.06	.06	.06				
14	1758 X		5	.09	.08	.06				
15	1760 X		37	1.84	2.12	.28				
16	1761 X		31	1.97	3.43	.07				
17	1762 X		3	.03	.03	.02				
	Repeat 1754 X		41	2.48	2.56	.12				

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.

DAB for PFB
Registered Assayer, Province of British Columbia



Member
Canadian Testing
Association

KAMLOOPS RESEARCH & ASSAY LABORATORY LTD.

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS B.C.
V1S 1A7

PHONE: (604) 372-2784 — TELEX: 048-8320

CERTIFICATE OF ASSAY

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS
METALLURGISTS 2

TO Cyprus Anvil Mining Corporation

Certificate No. K-3030

Date August 6, 1980

I hereby certify that the following are the results of assays made by us upon the herein described DY core samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		Ounces Per Ton	g/tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent
	<u>Standards</u>									
	100	90	5.58	8.92	.09					
	200	82	4.95	6.87	.16					
	300	44	2.23	4.38	.04					
	MP-1	59	1.77	15.90	-					
	KC-1	-	6.94	-	.11					

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.


Registered Assayer, Province of British Columbia

GEOCHEMICAL LOG

Kamloops Research and Assay Lab.

<u>From</u>	<u>To</u>	<u>Int.</u>	<u>Samp.</u> <u>No.</u>	<u>Ag/AA</u> <u>GM/MT</u>	<u>Ag/Fa</u> <u>GM/MT</u>	<u>Pb %</u>	<u>Zn %</u>	<u>Pb+Zn</u> <u>%</u>	<u>S.G.</u>	<u>Cu %</u>	<u>BaO %</u>	<u>Au</u> <u>GMS/MT</u>	<u>Po %</u>	<u>Py %</u>	<u>Hg %</u>	<u>Mn %</u>	<u>Rec.</u>	<u>Unit</u>
743.0	743.5	0.5	5145	77.0		5.50	7.96	13.46		0.07							0.5	4G4
743.5	743.8	0.3	5146	56.0		4.36	5.24	9.60		0.04							0.3	4E0
746.5	747.2	0.7	5147	116.0	115.0	7.15	10.20	17.35	3.92	0.13	14.6	0.62	2.6	12.8	.004		0.7	4G4
747.2	748.5	1.3	5148	22.0	20.0	1.73	2.37	4.10	2.79	0.04	2.1	0.30	3.8	4.0	.001		1.3	4A4
748.5	749.6	1.1	5149	71.0	65.0	4.87	6.64	11.51	4.45	0.14	13.8	0.96	3.6	20.4	.004		1.1	4G4
749.6	751.1	1.5	5150	40.0	36.0	2.42	1.92	4.34	4.22	0.28	0.1	2.54	8.5	30.5	.001		1.5	4E4
751.1	753.4	2.3	1744	84.0	84.0	5.72	6.26	11.98	4.38	0.11	16.8	0.82	3.1	19.4	.005		2.1	4G4
801.6	803.6	2.0	1745	3.0		0.08	0.12			0.06							1.9	4L6
803.6	805.6	2.0	1746	2.0		0.02	0.03			0.07							1.8	4L6
805.6	807.5	1.9	1747	2.0		0.09	0.15			0.05							1.9	4L6
810.0	810.9	0.9	1748	35.0		2.17	3.61	5.78		0.12							0.9	4A0
810.9	811.2	0.3	1749	62.0	53.0	3.85	9.02	12.87	3.30	0.01	0.17	0.62	1.5	13.5	.004		0.3	4A4
811.2	811.7	0.5	1750	38.0	33.0	3.07	11.10	14.17	4.58	0.03	3.1	0.69	0.8	30.9	.007		0.5	4E6
811.7	813.2	1.5	1751	51.0	50.0	4.12	4.89	9.01	4.46	0.12	26.6	0.75	5.1	16.6	.005			4G0
813.2	814.4	1.2	1752	56.0	52.0	3.67	5.23	8.90	4.13	0.18	17.5	0.96	4.9	16.1	.004			4G0
814.4	815.0	0.6	1753	58.0	51.0	3.42	5.50	8.92	3.78	0.03	0.9	0.75	1.0	24.0	.004			4C0
815.0	816.1	1.1	1754	41.0	38.0	2.48	2.56	5.04	3.22	0.12	0.2	0.69	1.5	10.0	.003			4A4
816.1	818.8	2.7	1755	11.0		0.61	0.36	0.97		0.18							2.6	4A0
818.8	820.5	1.7	1756	57.0		3.91	1.81	5.72		0.21							1.6	4A4
825.2	827.2	2.0	1761	31.0		1.97	3.43	5.40		0.07							1.9	4A0
827.2	828.0	0.8	1762	3.0		0.03	0.03			0.02							0.8	4A0
832.7	834.7	2.0	1757	2.0		0.06	0.06			0.06							2.0	4L6
834.7	836.7	2.0	1758	5.0		0.09	0.08			0.06							2.0	4L6
836.7	838.7	2.0	1759														2.0	4L6
850.7	851.2	0.5	1760	37.0		1.84	2.12	3.96		0.28							0.4	4D4

BEST SECTIONS

		Ag <u>GMS/MT</u>	<u>Pb %</u>	<u>Zn %</u>	<u>Pb+Zn</u>
746.5 - 753.4	6.9	63.9	4.26	5.04	9.30
810.9 - 815.0	4.1	52.7	3.73	6.14	9.87



Member
Canadian Testing
Association

KAMLOOPS RESEARCH & ASSAY LABORATORY LTD.

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS B.C.
V1S 1A7

PHONE: (604) 372-2784 — TELEX: 048-8320

CERTIFICATE OF ASSAY

**B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS
METALLURGISTS**

TO Cyprus Anvil Mining Corporation
330 - 355 Burrard Street
Vancouver, B.C. V6C 2G8

Certificate No. K-3035

Date January 21, 1981

I hereby certify that the following are the results of assays made by us upon the herein described _____ samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		Ounces Per Ton	grams per tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent
1	1809		15	.36	.39	.52				

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.


Registered Assayer, Province of British Columbia



KAMLOOPS RESEARCH & ASSAY LABORATORY LTD.

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS B.C.
V1S 1A7

PHONE: (604) 372-2784 — TELEX: 048-8320

CERTIFICATE OF ASSAY

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS
METALLURGISTS 3

TO Cyprus Anvil Mining Corporation

Certificate No. K-3428

Date December 18, 1980

I hereby certify that the following are the results of assays made by us upon the herein described _____ samples

Kral No.	Marked	GOLD grams per tonne	SILVER grams per tonne	Py Percent	Po Percent	BaO Percent	Hg Percent	S.G. Percent	Percent	Percent
41	X 1752	.96	52	16.1	4.9	17.5	.004	4.13		
42	1753	.75	51	24.0	1.0	0.9	.004	3.78		
43	1754	.69	38	10.0	1.5	0.2	.003	3.22>	*
44	1766	1.51	75	24.1	1.6	14.3	.006	3.90		
45	1767	.69	64	18.7	1.8	14.8	.006	4.43		
46	1768	.93	83	24.2	1.7	6.5	.006	4.29		
47	1769	.75	9	16.2	4.3	0.7	.002	3.10		
48	1770	1.17	108	16.2	1.4	24.4	.007	4.35		
49	1771	.82	106	17.0	4.2	20.9	.006	4.54		
50	1772	1.47	24	34.4	9.5	0.1	.003	4.28		
51	1773	.75	17	17.5	7.3	1.3	.002	3.62		
52	1774	.99	90	18.8	1.5	11.0	.008	4.23		
53	1775	2.84	140	31.7	.6	6.5	.007	5.10		
54	1776	1.37	73	36.0	.4	0.4	.006	4.63		
55	1777	.55	99	11.5	1.1	31.6	.007	4.51		
56	1778	.75	138	10.8	2.1	25.6	.008	4.75		
57	1779	1.16	77	21.6	1.0	13.3	.007	4.27		
58	1785	.69	109	15.7	1.4	22.2	.007	4.45		
59	1786	1.71	51	28.2	6.5	2.0	.004	4.50		
60	1787	.69	83	14.8	6.4	15.7	.004	4.25		

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.

[Signature]
Registered Assayer, Province of British Columbia



KAMLOOPS RESEARCH & ASSAY LABORATORY LTD.

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS B.C.
V1S 1A7

PHONE: (604) 372-2784 — TELEX: 048-8320

CERTIFICATE OF ASSAY

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS
METALLURGISTS 4

TO Cyprus Anvil Mining Corporation


Certificate No. K-3428

Date December 19, 1980

I hereby certify that the following are the results of assays made by us upon the herein described _____ samples

Kral No.	Marked	GOLD	SILVER	Py	Po	BaO	Hg	S.G.		
		grams per tonne	grams per tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent
61	X 1788	1.54	49	28.2	4.3	0.6	.003	4.15		
62	1789	1.30	51	28.9	6.0	0.1	.004	3.86		
63	1790	1.51	82	17.6	4.6	0.1	.006	4.39		
64	1839	.34	83	9.9	9.8	1.3	.003	3.45		
65	1840	.27	109	2.3	31.0	0.1	.003	3.89		
66	1841	1.17	83	7.9	8.7	1.5	.003	3.39		
67	1842	1.10	124	12.3	13.0	2.4	.002	4.15		
68	1843	.96	110	11.7	12.2	3.3	.002	4.12		
69	1844	.75	97	13.3	8.0	7.5	.002	4.15		
70	1845	.69	74	12.4	7.1	7.6	.003	3.74		
71	1846	.96	133	12.9	7.3	10.2	.003	3.94		
72	1847	1.51	122	12.2	13.5	3.9	.003	4.27		
73	1848	1.85	60	25.0	12.1	10.1	.002	4.33		
74	1851	1.78	103	14.4	10.1	9.6	.004	4.38		
75	1852	.34	136	10.4	13.6	6.7	.002	4.04		
76	1869	.96	88	15.0	1.4	21.0	.007	4.29		
77	1870	1.78	75	28.5	1.8	3.5	.005	4.31		
78	1871	1.03	116	7.9	1.1	30.8	.009	4.43		
79	1872	1.34	78	15.4	2.7	10.9	.005	4.14		
80	1873	1.78	105	15.0	2.2	15.9	.007	4.30		

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.


Registered Assayer, Province of British Columbia



KAMLOOPS RESEARCH & ASSAY LABORATORY LTD.

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS B.C.
V1S 1A7

PHONE: (604) 372-2784 — TELEX: 048-8320

CERTIFICATE OF ASSAY

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS
METALLURGISTS

TO Cyprus Anvil Mining Corporation

330 - 355 Burrard St.

Vancouver, B.C. V6C 2G8

Attention: Mr. Darryl Hanson

Certificate No. K-3049

Date August 21, 1980

I hereby certify that the following are the results of assays made by us upon the herein described DY core samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		g/tonne	g/tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent
1	X 1786	-	46	3.15	3.39	.34				
2	1787	-	94	5.42	8.20	.11				
3	1788	-	43	2.39	2.32	.33				
4	1789	-	50	4.18	3.87	.40				
5	1790	-	89	7.69	8.50	.18				
6	1791	-	19	.72	.77	.26				
7	1792	.446	22	1.12	1.22	.32				
8	1793	1.029	31	1.28	1.72	.33				
9	1794	.377	147	8.14	8.52	.09				
10	1795	.514	42	2.60	3.60	.15				
11	X 1796	.651	38	2.69	1.58	.18				
12	1797	.137	42	3.03	3.74	.05				
13	1798	.309	95	6.13	10.00	.13				
14	1799	.137	30	1.64	1.44	.14				
15	1800	.274	10	.35	.17	.09				
16	1811	.480	11	.22	.19	.33				
17	1812	.549	12	.18	.25	.28				
18	1813	.789	16	.29	.18	.29				
19	1814	.583	15	.15	.13	.31				
20	1815	-	15	.63	.08	.21				

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.

Registered Assayer, Province of British Columbia



KAMLOOPS RESEARCH & ASSAY LABORATORY LTD.

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS B.C.
V1S 1A7

PHONE: (604) 372-2784 — TELEX: 048-8320

CERTIFICATE OF ASSAY

**B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS
METALLURGISTS 2**

TO Cyprus Anvil Mining Corporation

Certificate No. K-3049

Date August 21, 1980

I hereby certify that the following are the results of assays made by us upon the herein described DY core samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		g/tonne	g/tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent
21	X 1816		11	.28	.10	.33				
22	1817		12	.45	.37	.26				
23	1818		7	.13	.13	.24				
24	1819		5	.09	.07	.08				
25	1820		5	.03	.06	.07				
26	1821		4	.05	.03	.05				
27	1822		4	.02	.02	.04				
28	1823		17	.84	1.07	.07				
29	1824		16	.83	1.46	.07				
30	1825		90	.61	6.98	.22				
31	X 1826		20	.28	.76	.48				
32	1827		22	.45	.60	.21				
33	1828		12	.82	.45	.08				
34	1829		28	1.82	2.54	.22				
35	1830		20	.88	1.40	.16				
36	1831		54	3.48	3.80	.24				
37	1832		11	.42	.25	.16				
38	1833		56	3.42	3.05	.32				
39	1834		2	.05	.02	.02				
40	1835		15	.76	.89	.10				

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.

DAB for PGB

Registered Assayer, Province of British Columbia



KAMLOOPS RESEARCH & ASSAY LABORATORY LTD.

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS B.C.
V1S 1A7

PHONE: (604) 372-2784 — TELEX: 048-8320

CERTIFICATE OF ASSAY

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS
METALLURGISTS 4

TO Cyprus Anvil Mining Corporation


Certificate No. K-3049

Date August 21, 1980

I hereby certify that the following are the results of assays made by us upon the herein described DY core samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		g/tonne	g/tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent
1	1801	.514 -								
2	1802	1.646 -								
3	1803	.823 -								
4	1804	.617 -								
5	1805	.686 -								
6	1806	.480 -								
7	1807	.309 -								
8	1808	.652 -								
9	1809	.514 -								
10	1810	.549 -								
	<u>Repeats</u>									
	1795									
	1815		42	2.59	3.63	.15				
	1839		15	.61	.08	.21				
	1847		90	6.40	4.85	.19				
			140	11.15	4.76	.15				

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.


Registered Assayer, Province of British Columbia



(F)
X-08

KAMLOOPS RESEARCH & ASSAY LABORATORY LTD.

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS B.C.
V1S 1A7

PHONE: (604) 372-2784 — TELEX: 048-8320

CERTIFICATE OF ASSAY

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS
METALLURGISTS

TO Cyprus Anvil Mining Corporation

330 - 355 Burrard St.

Vancouver, B.C. V6C 2G8

Certificate No. K-3035

Date August 8, 1980

I hereby certify that the following are the results of assays made by us upon the herein described DY core samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		Ounces Per Ton	g/tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent
1	X 1763		71	4.63	5.44	.034				
2	1764		13	.64	.82	.20				
3	1765		62	4.32	5.35	.23				
4	1766		75	3.79	5.35	.13				
5	1767		68	5.16	5.14	.51				
6	1768		84	7.05	6.92	.19				
7	1769		11	.45	.74	.19				
8	1770		118	7.26	10.56	.15				
9	1771		106	6.53	9.28	.18				
10	1772		19 23	.90	1.11	.38				
				.94						
11	X 1773		24	1.19	1.31	.17				
12	1774		82	5.58	9.28	.13				
13	1775		121	5.16	7.02	.36				
14	1776		71	4.10	6.13	.13				
15	1777		104	7.16	9.19	.04				
16	1778		155	10.10	9.77	.07				
17	1779		73	4.84	7.22	.25				
18	1780		31	1.49	1.76	.25				
19	1781		18	.69	.84	.26				
20	1782		90 88.0	5.26	7.22	.87				
					7.12	.08				

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.

DAB for OGB
Registered Assayer, Province of British Columbia



KAMLOOPS RESEARCH & ASSAY LABORATORY LTD.

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS B.C.
V1S 1A7

PHONE: (604) 372-2784 — TELEX: 048-8320

CERTIFICATE OF ASSAY

**B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS
METALLURGISTS 2**

TO Cyprus Anvil Mining Corporation

Certificate No. K-3035

Date August 8, 1980

I hereby certify that the following are the results of assays made by us upon the herein described DY core samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		Ounces Per Ton	g/tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent
21	X 1783		34	1.46	1.61	.26				
22	1784		33	1.80	1.60	.21				
23	<u>1785</u>		112	7.68	9.58	.11				
24	1801 X		34	2.00	4.07	.20				
25	1802		24	.96	1.29	.33				
26	1803		19	.81	.60	.28				
27	1804		46	2.74	3.67	.31				
28	1805		15	.55	.57	.21				
29	1806		6	.37	1.14	.25				
30	1807		11	.53	.85	.44				
31	1808 X		12	.36	.47	.52				
32	1810		10	.21	.23	.38				
	<u>Repeats</u>									
	X 1772		23	.94	1.11	.38				
	X 1782		88	5.26	7.12	.08				

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.

Daryl O'S
Registered Assayer, Province of British Columbia



KAMLOOPS RESEARCH & ASSAY LABORATORY LTD.

**B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS
METALLURGISTS 3**

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS B.C.
V1S 1A7

PHONE: (604) 372-2784 — TELEX: 048-8320

CERTIFICATE OF ASSAY

TO Cyprus Anvil Mining Corporation

Certificate No. K-3035

Date August 8, 1980

I hereby certify that the following are the results of assays made by us upon the herein described DY core samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		Ounces Per Ton	g/tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent
	<u>Standards</u>									
	100		95	5.37	8.89	.11				
	200		82	4.95	6.53	.15				
	300		40	2.32	4.46	.04				
	MP-1		58	1.89	16.18	-				
	KC-1		1120	6.95	19.62	.11				
	PTC 1		6	-	-	-				

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.

Registered Assayer, Province of British Columbia

GEOCHEMICAL LOG

Kamloops Research and Assay Lab.

<u>From</u>	<u>To</u>	<u>Int.</u>	<u>Samp.</u> <u>No.</u>	<u>Ag/AA</u> <u>GM/MT</u>	<u>Ag/Fa</u> <u>GM/MT</u>	<u>Pb %</u>	<u>Zn %</u>	<u>Pb+Zn</u> <u>%</u>	<u>S.G.</u>	<u>Cu %</u>	<u>BaO %</u>	<u>Au</u> <u>GMS/MT</u>	<u>Po %</u>	<u>Py %</u>	<u>Hg %</u>	<u>Mn %</u>	<u>Rec.</u>	<u>Unit</u>
822.3	823.0	0.7	1763	71.0		4.63	5.44	10.07		0.34							0.6	4G4
823.0	826.5	3.5	1764	13.0		0.64	0.82	1.46		0.20							3.5	4L6
826.5	827.0	0.5	1765	62.0		4.32	5.35	9.67		0.23							0.3	4G1
829.2	829.7	0.5	1766	75.0	75.0	3.79	5.35	9.14	3.90	0.13	14.3	1.51	1.6	24.1	.006		0.5	4G4
829.7	830.5	0.8	1767	68.0	64.0	5.16	5.14	10.30	4.43	0.51	14.8	0.69	1.8	14.7	.006		0.8	4D4
830.5	831.4	0.9	1768	84.0	83.0	7.05	6.92	13.97	4.29	0.19	6.5	0.93	1.7	24.2	.006		0.8	4G0
831.4	831.9	0.5	1769	11.0	9.0	0.45	0.74	1.19	3.10	0.19	0.7	0.75	4.3	16.2	.002		0.5	4A9
831.9	832.9	1.0	1770	118.0	108.0	7.26	10.56	17.82	4.35	0.15	24.4	1.17	1.4	16.2	.007		1.0	4G4
832.9	834.4	1.5	1771	106.0	106.0	6.53	9.28	15.81	4.54	0.18	20.9	0.82	4.2	17.0	.006		1.5	4G4
834.4	834.9	0.5	1772	23.0	24.0	0.94	1.11	2.05	4.28	0.38	0.1	1.47	9.5	34.4	.003		0.5	4E8
834.9	835.2	0.3	1773	24.0	17.0	1.19	1.31	2.50	3.62	0.17	1.3	0.75	7.3	17.5	.002		0.2	4C7
835.2	835.9	0.7	1774	82.0	90.0	5.58	9.28	14.86	4.23	0.13	11.0	0.99	1.5	18.8	.008		0.7	4G4
835.9	836.6	0.7	1775	121.0	140.0	5.16	7.02	12.18	5.10	0.36	6.5	2.84	0.6	31.7	.007		0.7	4G0
836.6	837.5	0.9	1776	71.0	73.0	4.10	6.13	10.23	4.63	0.13	0.4	1.37	0.4	36.0	.006		0.9	4E0
837.5	839.5	2.0	1777	104.0	99.0	7.16	9.19	16.35	4.51	0.04	31.6	0.55	1.1	11.5	.007		2.0	4G4
839.5	841.1	1.6	1778	155.0	138.0	10.10	9.77	19.87	4.75	0.07	25.6	0.75	2.1	10.8	.008		1.6	4G4
841.1	841.8	0.7	1779	73.0	77.0	4.84	7.22	12.06	4.27	0.25	13.3	1.16	1.0	21.6	.007		0.5	4G1
841.8	842.9	1.1	1780	31.0		1.49	1.76	3.25		0.25							1.1	4C7
842.9	845.2	2.3	1781	18.0		0.69	0.84	1.53		0.26							2.0	4E8
845.2	845.5	0.3	1782	88.0		5.26	7.12	12.38		0.08							0.3	4G4
845.5	847.0	1.5	1783	34.0		1.46	1.61	3.07		0.26							1.4	4E8
847.0	847.6	0.6	1784	33.0		1.80	1.60	3.40		0.21							0.6	4C0
847.6	848.5	0.9	1785	112.0	109.0	7.68	9.58	17.26	4.45	0.11	22.2	0.69	1.4	15.7	.007		0.9	4G4
848.5	850.6	2.1	1786	46.0	51.0	3.15	3.39	6.54	4.50	0.34	2.0	1.71	6.5	28.2	.004		2.1	4E4
860.5	861.5	1.0	1787	94.0	83.0	5.42	8.20	13.62	4.25	0.11	15.7	0.69	6.4	14.8	.004		0.5	4G4
861.5	863.5	2.0	1788	43.0	49.0	2.39	2.32	4.71	4.15	0.33	0.6	1.54	4.3	28.2	.003			4E1
863.5	865.1	1.6	1789	50.0	51.0	4.18	3.87	8.05	3.86	0.40	0.1	1.30	6.0	28.9	.004		1.3	4E1
865.1	865.8	0.7	1790	89.0	82.0	7.69	8.50	16.19	4.39	0.18	0.1	1.51	4.6	17.6	.006		0.7	4G0
865.8	866.5	0.7	1791	19.0		0.72	0.77	1.49		0.26							0.7	4E8
866.5	867.8	1.3	1792	22.0		1.12	1.22	2.34		0.32		0.446					1.0	4C7
867.8	869.3	1.5	1793	31.0		1.28	1.72	3.00		0.33		1.029					1.4	4E0

DDH 80-X-08

GEOCHEMICAL LOG

Kamloops Research and Assay Lab.

<u>From</u>	<u>To</u>	<u>Int.</u>	<u>Samp.</u> <u>No.</u>	<u>Ag/AA</u> <u>GM/MT</u>	<u>Ag/Fa</u> <u>GM/MT</u>	<u>Pb %</u>	<u>Zn %</u>	<u>Pb+Zn</u> <u>%</u>	<u>S.G.</u>	<u>Cu %</u>	<u>BaO %</u>	<u>Au</u> <u>GMS/MT</u>	<u>Po %</u>	<u>Py %</u>	<u>Hg %</u>	<u>Mn %</u>	<u>Rec.</u>	<u>Un</u>
869.3	869.9	0.6	1794	147.0		8.14	8.52	16.66		0.09		0.377					0.6	4G
869.9	871.9	2.0	1795	42.0		2.60	3.60	6.20		0.15		0.514					2.0	4C
871.9	873.9	2.0	1796	38.0		2.69	1.58	4.27		0.18		0.651					2.0	4C
873.9	874.9	1.0	1801	34.0		2.00	4.07	6.07		0.20		0.514					1.0	4C
874.9	876.9	2.0	1802	24.0		0.96	1.29	2.25		0.33		1.646					1.9	4C
876.9	878.9	2.0	1803	19.0		0.81	0.60	1.41		0.28		0.823					1.8	4C
878.9	880.9	2.0	1804	46.0		2.74	3.67	6.41		0.31		0.617					1.9	4C
880.9	882.9	2.0	1805	15.0		0.55	0.57	1.12		0.21		0.686					1.9	4C
882.9	884.9	2.0	1806	6.0		0.37	1.14	1.51		0.25		0.480					2.0	4C
884.9	886.9	2.0	1807	11.0		0.53	0.85			0.44		0.309					1.9	4C
886.9	888.9	2.0	1808	12.0		0.36	0.47			0.52		0.652					2.0	4C
888.9	890.3	1.4	1809	15.0		0.36	0.39			0.52		0.514					1.4	4C
890.3	891.0	0.7	1810	10.0		0.21	0.23			0.38		0.549					0.7	4C
891.0	893.0	2.0	1811	11.0		0.22	0.19			0.33		0.480					2.0	4C
893.0	895.0	2.0	1812	12.0		0.18	0.25			0.28		0.549					2.0	4C
895.0	896.6	1.6	1813	16.0		0.29	0.18			0.29		0.789					1.6	4C
896.6	898.6	2.0	1814	15.0		0.15	0.13			0.31		0.583					1.9	4C
898.6	899.3	0.7	1815	15.0		0.63	0.08			0.21							0.6	4A
899.3	899.7	0.4	1816	11.0		0.28	0.10			0.33							0.4	4A
899.7	901.0	1.3	1817	12.0		0.45	0.37			0.26							1.2	4C
901.0	903.0	2.0	1818	7.0		0.13	0.13			0.24							2.0	4L
903.0	903.9	0.9	1819	5.0		0.09	0.07			0.08							0.8	4L
903.9	905.9	2.0	1820	5.0		0.03	0.06			0.07							1.9	4L
905.9	907.6	1.7	1821	4.0		0.05	0.03			0.05							1.5	4L
907.6	908.1	0.5	1822	4.0		0.02	0.02			0.04							0.4	4L
920.1	920.5	0.4	1797	42.0		3.03	3.74	6.77		0.05		0.137					0.4	4A
920.5	921.2	0.7	1798	95.0		6.13	10.00	16.13		0.13		0.309					0.6	4D
922.6	924.6	2.0	1799	30.0		1.64	1.44	3.08		0.14		0.137					1.9	4A
924.6	925.5	0.9	1800	10.0		0.35	0.17			0.09		0.274					0.5	4A



KAMLOOPS RESEARCH & ASSAY LABORATORY LTD.

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS B.C.
V1S 1A7

PHONE: (604) 372-2784 — TELEX: 048-8320

CERTIFICATE OF ASSAY

**B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS
METALLURGISTS**

TO Cyprus Anvil Mining Corporation


Certificate No. K-3428

Date December 19, 1980

I hereby certify that the following are the results of assays made by us upon the herein described _____ samples

Kral No.	Marked	GOLD	SILVER	Py	Po	BaO	Hg	S.G.		
		grams per tonne	grams per tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent
08	X 1788	1.54	49	28.2	4.3	0.6	.003	4.15		
	1789	1.30	51	28.9	6.0	0.1	.004	3.86		
	1790	1.51	82	17.6	4.6	0.1	.006	4.39		
64	1839	.34	83	9.9	9.8	1.3	.003	3.45		
65	1840	.27	109	2.3	31.0	0.1	.003	3.89		
66	1841	1.17	83	7.9	8.7	1.5	.003	3.39		
67	1842	1.10	124	12.3	13.0	2.4	.002	4.15		
68	1843	.96	110	11.7	12.2	3.3	.002	4.12		
69	1844	.75	97	13.3	8.0	7.5	.002	4.15		
70	1845	.69	74	12.4	7.1	7.6	.003	3.74		
09	71	1846	.96	133	12.9	7.3	10.2	.003	3.94	
	72	1847	1.51	122	12.2	13.5	3.9	.003	4.27	
	73	1848	1.85	60	25.0	12.1	10.1	.002	4.33	
	74	1851	1.78	103	14.4	10.1	9.6	.004	4.38	
	75	1852	.34	136	10.4	13.6	6.7	.002	4.04	
76	1869	.96	88	15.0	1.4	21.0	.007	4.29		
77	1870	1.78	75	28.5	1.8	3.5	.005	4.31		
78	1871	1.03	116	7.9	1.1	30.8	.009	4.43		
10	79	1872	1.34	78	15.4	2.7	10.9	.005	4.14	
	80	1873	1.78	105	15.0	2.2	15.9	.007	4.30	

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.


Registered Assayer, Province of British Columbia



KAMLOOPS RESEARCH & ASSAY LABORATORY LTD.

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS B.C.
V1S 1A7

PHONE: (604) 372-2784 — TELEX: 048-8320

CERTIFICATE OF ASSAY

**B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS
METALLURGISTS**

CALCULATION ERROR ON ORIGINAL SHEET

TO Cyprus Anvil Mining Corporation
330 - 355 Burrard Street
Vancouver, B.C. V6C 2G8

X-09

Certificate No. K-3049

Date December 9, 1980

I hereby certify that the following are the results of assays made by us upon the herein described _____ samples

Kral No.	Marked	GOLD	SILVER						
		Ounces Per Ton	g/tonne	Percent	Percent	Percent	Percent	Percent	Percent
1	1840		120						
2	1842		147						
3	1843		121						
4	1847		135						
5	1851		164						
6	1853		153						

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.

Registered Assayer, Province of British Columbia



KAMLOOPS RESEARCH & ASSAY LABORATORY LTD.

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS B.C.
V1S 1A7

PHONE: (604) 372-2784 — TELEX: 048-8320

CERTIFICATE OF ASSAY

**B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS
METALLURGISTS**

TO Cyprus Anvil Mining Corporation
330 - 355 Burrard St.
Vancouver, B.C.

Certificate No. K-3149
Date September 12, 1980

I hereby certify that the following are the results of assays made by us upon the herein described DY core samples

Kral No	Marked	GOLD	SILVER	Pb	Zn	Cu				
		Ounces Per Ton	g/tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent
1	1853 X		21	1.72	1.21	.11				
2	1854		9	.56	.71	.09				
3	1855		4	.25	.30	.02				
4	1856		25	.19	2.80	.20				
5	1857		63	3.24	3.95	.25				
6	1858		4	.03	.05	.15				
7	1859		5	.26	.21	.15				
8	1860		5	.07	.06	.10				
9	1861		1	.04	.11	.10				
10	1862		2	.03	.07	.15				
11	1863 X		3	.02	.06	.14				
12	1864		6	.05	.11	.11				
13	1865		5	.07	.12	.07				
14	1866		5	.10	.14	.06				
15	1867		27	2.31	3.19	.06				
16	1868		46	3.67	5.75	.05				
17	1869		78	6.80	6.74	.07				
18	1870		73	3.90	4.66	.09				
19	1871		115	7.80	7.92	.11				
20	1872		113	6.10	4.83	.09				

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.

[Signature]

Registered Assayer, Province of British Columbia



KAMLOOPS RESEARCH & ASSAY LABORATORY LTD.

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS B.C.
V1S 1A7

PHONE: (604) 372-2784 — TELEX: 048-8320

CERTIFICATE OF ASSAY

**B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS
METALLURGISTS 2**

TO Cyprus Anvil Mining Corporation

Certificate No. K-3049

Date August 21, 1980

I hereby certify that the following are the results of assays made by us upon the herein described DY core samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		g/tonne	g/tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent
21	X 1816		11	.28	.10	.33				
22	1817		12	.45	.37	.26				
23	1818		7	.13	.13	.24				
24	1819		5	.09	.07	.08				
25	1820		5	.03	.06	.07				
26	1821		4	.05	.03	.05				
27	1822		4	.02	.02	.04				
28	1823		17	.84	1.07	.07				
29	1824		16	.83	1.46	.07				
30	1825		90	.61	6.98	.22				
31	X 1826		20	.28	.76	.48				
32	1827		22	.45	.60	.21				
33	1828		12	.82	.45	.08				
34	1829		28	1.82	2.54	.22				
35	1830		20	.88	1.40	.16				
36	1831		54	3.48	3.80	.24				
37	1832		11	.42	.25	.16				
38	1833		56	3.42	3.05	.32				
39	1834		2	.05	.02	.02				
40	1835		15	.76	.89	.10				

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.

DAB for PGB
Registered Assayer, Province of British Columbia



KAMLOOPS RESEARCH & ASSAY LABORATORY LTD.

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS B.C.
V1S 1A7

PHONE: (604) 372-2784 — TELEX: 048-8320

CERTIFICATE OF ASSAY

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS
METALLURGISTS 3

TO Cyprus Anvil Mining Corporation


Certificate No. K-3049

Date August 21, 1980

I hereby certify that the following are the results of assays made by us upon the herein described DY core samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		g/tonne	g/tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent
41	X 1836		3	.11	.10	.02				
42	1837		25	1.68	1.75	.39				
43	1838		20	1.37	1.25	.28				
44	1839		96	6.58	5.06	.20				
45	1840		129	9.37	4.68	.13				
46	1841		90	7.40	4.11	.06				
47	1842		158	11.78	5.63	.11				
48	1843		130	11.69	5.31	.10				
49	1844		110	9.77	5.29	.03				
50	1845		80	6.45	6.53	.05				
51	X 1846		185	11.28	4.47	.09				
52	1847		145	11.38	4.94	.16				
53	1848		64	4.34	2.29	.34				
54	1849		31	1.59	1.15	.63				
55	1850		27	.98	1.08	.11				
56	1851		176	9.12	5.94	.13				
57	1852		164	10.71	7.22	.09				

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.


Registered Assayer, Province of British Columbia

GEOCHEMICAL LOG

Kamloops Research and Assay Lab.

<u>From</u>	<u>To</u>	<u>Int.</u>	<u>Samp.</u> <u>No.</u>	<u>Ag/AA</u> <u>GM/MT</u>	<u>Ag/Fa</u> <u>GM/MT</u>	<u>Pb %</u>	<u>Zn %</u>	<u>Pb+Zn</u> <u>%</u>	<u>S.G.</u>	<u>Cu %</u>	<u>BaO %</u>	<u>Au</u> <u>GMS/MT</u>	<u>Po %</u>	<u>Py %</u>	<u>Hg %</u>	<u>Mn %</u>	<u>Rec.</u>	<u>Unit</u>
637.5	639.2	1.7	1827	22.0		0.45	0.60	1.05		0.21							1.7	4C8
639.2	640.7	1.5	1828	12.0		0.82	0.45	1.27		0.08							1.5	4L7
640.7	641.6	0.9	1829	28.0		1.82	2.54	4.36		0.22							0.8	4C8
647.3	648.3	1.0	1830	20.0		0.88	1.40	2.28		0.16							0.9	4A0
650.8	651.3	0.5	1831	54.0		3.48	3.80	7.28		0.24							0.5	4E8
651.3	651.8	0.5	1832	11.0		0.42	0.25	0.67		0.16							0.5	4C7
651.8	653.0	1.2	1833	56.0		3.42	3.05	6.47		0.32							1.1	4G4
658.1	659.1	1.0	1834	2.0		0.05	0.02			0.02							0.8	4L7
659.1	600.1	1.0	1835	15.0		0.76	0.89			0.10							1.0	4L1
660.1	662.6	2.5	1836	3.0		0.11	0.10			0.02							1.9	4L7
663.6	665.1	1.5	1837	25.0		1.68	1.75	3.43		0.39							1.5	4K8
677.1	678.4	1.3	1838	20.0		1.37	1.25	2.62		0.28							1.3	4K0
725.0	726.8	1.8	1839	96.0	83.0	6.58	5.06	11.64	3.45	0.20	1.3	0.34	9.8	9.9	.003		1.8	4C0
726.8	727.0	0.2	1840	129.0	120.0	9.37	4.68	14.05	3.89	0.13	0.1	0.27	31.0	2.3	.003		0.2	4H0
729.1	731.1	2.0	1841	90.0	83.0	7.40	4.11	11.51	3.39	0.06	1.5	1.17	8.7	7.9	.003		2.0	4K4
731.1	733.1	2.0	1842	158.0	147.0	11.78	5.63	17.41	4.15	0.11	2.4	1.10	13.0	12.3	.002		2.0	4K4
733.1	735.1	2.0	1843	130.0	121.0	11.69	5.31	17.00	4.12	0.10	3.3	0.96	12.2	11.7	.002		2.0	4K4
735.1	735.8	0.7	1844	110.0	97.0	9.77	5.29	15.06	4.15	0.03	7.5	0.75	8.0	13.3	.002		0.7	4K4
735.8	737.8	2.0	1845	80.0	74.0	6.45	6.53	12.98	3.74	0.05	7.6	0.69	7.1	12.4	.003		2.0	4G4
737.8	739.8	2.0	1846	185.0	133.0	11.28	4.47	15.75	3.94	0.09	10.2	0.96	7.3	12.9	.003		1.3	4G4
739.8	741.1	1.3	1847	145.0	135.0	11.38	4.94	16.32	4.27	0.16	3.9	1.51	13.5	12.2	.003		1.2	4G4
741.1	743.1	2.0	1848	64.0	60.0	4.34	2.29	6.63	4.33	0.34	L 0.1	1.85	12.1	25.0	.002		1.7	4E8
743.1	744.9	1.8	1849	31.0		1.59	1.15	2.74		0.63							1.8	4E8
744.9	745.2	0.3	1850	27.0		0.98	1.08	2.06		0.11							0.2	4H0



KAMLOOPS RESEARCH & ASSAY LABORATORY LTD.

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS B.C.
V1S 1A7

PHONE: (604) 372-2784 — TELEX: 048-8320

CERTIFICATE OF ASSAY

**B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS
METALLURGISTS** 4

TO Cyprus Anvil Mining Corporation


Certificate No. K-3428

Date December 19, 1980

I hereby certify that the following are the results of assays made by us upon the herein described _____ samples

Kral No.	Marked	GOLD	SILVER	Py	Po	BaO	Hg	S.G.		
		grams per tonne	grams per tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent
08	X 1788	1.54	49	28.2	4.3	0.6	.003	4.15		
	1789	1.30	51	28.9	6.0	0.1	.004	3.86		
	1790	1.51	82	17.6	4.6	0.1	.006	4.39		
64	1839	.34	83	9.9	9.8	1.3	.003	3.45		
65	1840	.27	109	2.3	31.0	0.1	.003	3.89		
66	1841	1.17	83	7.9	8.7	1.5	.003	3.39		
67	1842	1.10	124	12.3	13.0	2.4	.002	4.15		
68	1843	.96	110	11.7	12.2	3.3	.002	4.12		
69	1844	.75	97	13.3	8.0	7.5	.002	4.15		
70	1845	.69	74	12.4	7.1	7.6	.003	3.74		
09	1846	.96	133	12.9	7.3	10.2	.003	3.94		
	1847	1.51	122	12.2	13.5	3.9	.003	4.27		
	1848	1.85	60	25.0	12.1	10.1	.002	4.33		
	1851	1.78	103	14.4	10.1	9.6	.004	4.38		
	1852	.34	136	10.4	13.6	6.7	.002	4.04		
76	1869	.96	88	15.0	1.4	21.0	.007	4.29		
77	1870	1.78	75	28.5	1.8	3.5	.005	4.31		
10	1871	1.03	116	7.9	1.1	30.8	.009	4.43		
	1872	1.34	78	15.4	2.7	10.9	.005	4.14		
	1873	1.78	105	15.0	2.2	15.9	.007	4.30		

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.


Registered Assayer, Province of British Columbia



Member
Canadian Testing
Association

KAMLOOPS RESEARCH & ASSAY LABORATORY LTD.

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS B.C.
V1S 1A7

PHONE: (604) 372-2784 — TELEX: 048-8320

CERTIFICATE OF ASSAY

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS
METALLURGISTS 5

TO Cyprus Anvil Mining Corporation


Certificate No. K-3428

Date December 19, 1980

I hereby certify that the following are the results of assays made by us upon the herein described samples

Kral No.	Marked	GOLD	SILVER	Py	Po	BaO	Hg	S.G.		
		grams per tonne	grams per tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent
81	X 1874	1.10	99	9.4	1.3	31.6	.009	4.46		
82	1875	1.03	122	7.6	1.2	30.5	.008	4.38		
83	1876	2.06	112	29.0	2.9	1.9	.004	4.41		
84	1877	1.99	102	14.5	1.1	24.8	.006	4.40		
85	1878	1.65	46	28.9	1.5	7.1	.003	3.83		
86	1879	1.54	76	30.4	1.6	1.9	.006	5.38		
87	1880	1.37	80	19.7	.9	22.7	.006	4.54		
88	1881	1.65	70	28.0	2.0	2.7	.005	4.34		
89	1882	1.99	76	32.8	1.5	4.4	.005	4.60		
90	1883	1.44	42	10.4	2.4	2.6	.004	3.22		
91	1884	.51	26	7.4	.9	0.7	.003	2.82		
92	1885	1.10	98	25.1	2.1	4.3	.004	4.20		
93	1894	1.10	44	31.5	4.1	1.8	.001	4.52		
11 94	1895	1.03	82	18.6	2.2	23.7	.003	4.47		
95	1941	.58	64	13.5	4.3	29.3	.003	4.51		
96	1942	.86	48	19.8	7.3	18.8	.002	4.26		
13 97	1943	.58	46	19.4	3.7	22.3	.004	4.41		
98	1944	.58	46	9.5	2.0	0.9	.003	3.03		
99	2006	.69	108	13.1	2.0	3.2	.002	3.51		
12 100	2007	.58	50	17.2	3.4	0.6	.002	3.50		

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.


Registered Assayer, Province of British Columbia



KAMLOOPS RESEARCH & ASSAY LABORATORY LTD.

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS B.C.

V1S 1A7

PHONE: (604) 372-2784 — TELEX: 048-8320

CERTIFICATE OF ASSAY

**B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS
METALLURGISTS**

TO Cyprus Anvil Mining Corporation
330 - 355 Burrard St.
Vancouver, B.C.

Certificate No. K-3149

Date September 12, 1980

I hereby certify that the following are the results of assays made by us upon the herein described DY core samples

Kral No	Marked	GOLD	SILVER	Pb	Zn	Cu				
		Ounces Per Ton	g/tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent
1	1853 X		21	1.72	1.21	.14				
2	1854		3	.56	.71	.09				
3	1855		4	.25	.30	.02				
4	1856		25	.19	2.80	.20				
5	1857		63	3.24	3.95	.35				
6	1858		4	.03	.05	.15				
7	1859		5	.26	.21	.15				
8	1860		5	.03	.06	.10				
9	1861		1	.04	.11	.10				
10	1862		2	.03	.07	.15				
11	1863 X		3	.02	.06	.14				
12	1864		6	.05	.11	.11				
13	1865		5	.07	.12	.07				
14	1866		5	.10	.14	.06				
15	1867		27	2.31	3.19	.06				
16	1868		46	3.67	5.75	.05				
17	1869		78	6.20	6.74	.07				
18	1870		73	3.90	4.66	.09				
19	1871		115	7.80	7.92	.11				
20	1872		113	6.10	4.83	.21				

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.

Registered Assayer, Province of British Columbia



KAMLOOPS RESEARCH & ASSAY LABORATORY LTD.

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS B.C.
V1S 1A7

PHONE: (604) 372-2784 — TELEX: 048-8320

CERTIFICATE OF ASSAY

**B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS
METALLURGISTS 3**

TO Cyprus Anvil Mining Corporation

Certificate No. K-3149

Date September 12, 1980

I hereby certify that the following are the results of assays made by us upon the herein described DY core samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		Ounces Per Ton	g/tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent
41	1893 X		24	1.99	3.55	.09				
42	1894		46	3.77	2.88	.18				
43	1895		90	5.15	5.43	.20				
44	1896		21	.51	.46	.40				
45	1897		2	.05	.04	.01				
46	1898		12	.18	.06	.14				
47	1899		11	.11	.06	.13				
48	1900		13	.65	.54	.33				
49	1901		4	.12	.20	.02				
50	1902		12	.74	1.32	.05				
51	1903 X		29	2.02	2.40	.04				
52	1904		28	2.36	2.51	.03				
53	1905		30	2.21	4.85	.03				
54	1906		31	2.19	2.76	.05				
55	1907		9	.33	.72	.10				
56	1908		4	.23	.31	.02				
57	1909		4	.29	.17	.03				
58	1910		11	.54	.63	.16				
59	1911		2	.04	.09	.03				
60	1912		28	1.95	3.10	.12				

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.

R. Brown

Registered Assayer, Province of British Columbia

DDH 80-X-10

GEOCHEMICAL LOG

Kamloops Research and Assay Lab.

From	To	Int.	Samp. No.	Ag/AA GM/MT	Ag/Fa GM/MT	Pb %	Zn %	Pb+Zn %	S.G.	Cu %	BaO %	Au GMS/MT	Po %	Py %	Hg %	Mn %	Rec.	Und
858.6	860.8	2.2	1857	63.0		3.24	3.95	7.19		0.35							2.2	4H1
860.8	862.4	1.6	1858	4.0		0.03	0.05			0.15							1.6	4L1
862.4	864.4	2.0	1859	5.0		0.26	0.21			0.15							2.0	4L1
864.4	866.4	2.0	1860	5.0		0.03	0.06			0.10							2.0	4L1
866.4	868.4	2.0	1861	1.0		0.04	0.11			0.10							2.0	4L1
868.4	870.4	2.0	1862	2.0		0.03	0.07			0.15							1.9	4L1
870.4	872.4	2.0	1863	3.0		0.02	0.06			0.14							2.0	4L1
874.4	876.9	2.5	1864	6.0		0.05	0.11			0.11							2.4	4L1
876.9	877.9	1.0	1865	5.0		0.07	0.12			0.07							1.0	4L1
877.9	879.8	1.9	1866	5.0		0.10	0.14			0.06							1.9	4L1
879.8	881.5	1.7	1867	27.0		2.31	3.19	5.50		0.06							1.7	4AC
881.5	881.8	0.3	1868	46.0		3.67	5.75	9.42		0.05							0.3	4CC
909.8	910.6	0.8	1869	78.0	88.0	6.20	6.74	12.94	4.29	0.07	21.0	0.96	1.4	15.0	.007		0.8	4G4
910.6	911.3	0.7	1870	73.0	75.0	3.90	4.66	8.56	4.31	0.09	3.5	1.78	1.8	28.5	.005		0.7	4E1
911.3	912.5	1.2	1871	115.0	116.0	7.80	7.92	15.72	4.43	0.11	30.8	1.03	1.1	7.9	.009		1.1	4G4
912.5	912.9	0.4	1872	113.0	78.0	6.10	4.83	10.93	4.14	0.21	10.9	1.34	2.7	15.4	.005		0.4	4K6
912.9	913.5	0.6	1873	140.0	105.0	7.20	7.46	14.66	4.30	0.25	15.9	1.78	2.2	15.0	.007		0.6	4G4
913.5	915.5	2.0	1874	121.0	99.0	7.10	10.40	17.50	4.46	0.14	31.6	1.10	1.3	9.4	.009		2.0	4G4
915.5	917.1	1.6	1875	121.0	122.0	6.60	10.70	17.30	4.38	0.15	30.5	1.03	1.2	7.6	.008		1.5	4G4
917.1	918.7	1.6	1876	116.0	112.0	4.90	4.04	8.94	4.41	0.27	1.9	2.06	2.9	29.0	.004		1.5	4E1
918.7	919.1	0.4	1877	103.0	102.0	6.80	8.71	15.51	4.40	0.21	24.8	1.99	1.1	14.5	.006		0.4	4G4
919.1	921.1	2.0	1878	40.0	46.0	2.47	3.84	6.31	3.83	0.22	7.1	1.65	1.5	28.9	.003		2.0	4E1
921.1	922.3	1.2	1879	66.0	76.0	4.87	7.10	11.97	5.38	0.16	1.9	1.54	1.6	30.4	.006		1.2	4E1
922.3	922.6	0.3	1880	73.0	80.0	4.98	7.70	12.68	4.54	0.13	22.7	1.37	0.9	19.7	.006		0.3	4G4
922.6	924.6	2.0	1881	65.0	70.0	4.38	6.35	10.73	4.34	0.29	2.7	1.65	2.0	28.0	.005		2.0	4E0
924.6	925.8	1.2	1882	68.0	76.0	3.47	4.81	8.28	4.60	0.29	4.4	1.99	1.5	32.8	.005		1.2	4E0
925.8	926.7	0.9	1883	42.0	42.0	2.87	5.55	8.42	3.22	0.14	2.6	1.44	2.4	10.4	.004		0.8	4D0
926.7	928.2	1.5	1884	25.0	26.0	2.09	4.01	6.10	2.82	0.02	0.7	0.51	0.9	7.4	.003		1.5	4A4
928.2	928.6	0.4	1885	99.0	98.0	3.22	5.18	8.40	4.20	0.20	4.3	1.10	2.1	25.1	.004		0.4	4G0
928.6	929.0	0.4	1886	15.0		0.14	0.08	0.22		0.33							0.4	4K0



Member
Canadian Testing
Association

KAMLOOPS RESEARCH & ASSAY LABORATORY LTD.

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS B.C.
V1S 1A7

PHONE: (604) 372-2784 — TELEX: 048-8320

CERTIFICATE OF ASSAY

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS
METALLURGISTS 5

TO Cyprus Anvil Mining Corporation

Certificate No. K-3428

Date December 19, 1980

I hereby certify that the following are the results of assays made by us upon the herein described samples

Kral No.	Marked	GOLD	SILVER	Py	Po	BaO	Hg	S.G.		
		grams per tonne	grams per tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent
81	X 1874	1.10	99	9.4	1.3	31.6	.009	4.46		
82	1875	1.03	122	7.6	1.2	30.5	.008	4.38		
83	1876	2.06	112	29.0	2.9	1.9	.004	4.41		
84	1877	1.99	102	14.5	1.1	24.8	.006	4.40		
85	1878	1.65	46	28.9	1.5	7.1	.003	3.83		
86	1879	1.54	76	30.4	1.6	1.9	.006	5.38		
87	1880	1.37	80	19.7	.9	22.7	.006	4.54		
88	1881	1.65	70	28.0	2.0	2.7	.005	4.34		
89	1882	1.99	76	32.8	1.5	4.4	.005	4.60		
90	1883	1.44	42	10.4	2.4	2.6	.004	3.22		
91	1884	.51	26	7.4	.9	0.7	.003	2.82		
92	1885	1.10	98	25.1	2.1	4.3	.004	4.20		
93	1894	1.10	44	31.5	4.1	1.8	.001	4.52		
94	1895	1.03	82	18.6	2.2	23.7	.003	4.47		
95	1941	.58	64	13.5	4.3	29.3	.003	4.54		
96	1942	.86	48	19.8	7.3	18.8	.002	4.26		
97	1943	.58	46	19.4	3.7	22.3	.004	4.41		
98	1944	.58	46	9.5	2.0	0.9	.003	3.03		
99	2006	.69	108	13.1	2.0	3.2	.002	3.51		
100	2007	.58	50	17.2	3.4	0.6	.002	3.50		

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.

[Signature]
Registered Assayer, Province of British Columbia



KAMLOOPS RESEARCH & ASSAY LABORATORY LTD.

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS B.C.
V1S 1A7

PHONE: (604) 372-2784 — TELEX: 048-8320

CERTIFICATE OF ASSAY

**B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS
METALLURGISTS 3**

TO Cyprus Anvil Mining Corporation

Certificate No. K-3149

Date September 12, 1980

I hereby certify that the following are the results of assays made by us upon the herein described DY core samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		Ounces Per Ton	g/tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent
41	1893 X		24	1.99	3.55	.09				
42	1894		46	3.77	2.88	.18				
43	1895		90	5.15	5.43	.20				
44	1896		21	.51	.46	.40				
45	1897		2	.05	.04	.01				
46	1898		12	.18	.06	.14				
47	1899		11	.11	.06	.13				
48	1900		13	.65	.54	.33				
49	1901		4	.12	.20	.02				
50	1902		12	.74	1.32	.05				
51	1903 X		29	2.02	2.40	.04				
52	1904		28	2.36	2.51	.03				
53	1905		30	2.21	4.85	.03				
54	1906		31	2.19	2.76	.05				
55	1907		9	.33	.72	.10				
56	1908		4	.23	.31	.02				
57	1909		4	.29	.17	.03				
58	1910		11	.54	.63	.16				
59	1911		2	.04	.09	.03				
60	1912		28	1.95	3.10	.12				

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.

Registered Assayer, Province of British Columbia



KAMLOOPS RESEARCH & ASSAY LABORATORY LTD.

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS B.C.
V1S 1A7

PHONE: (604) 372-2784 — TELEX: 048-8320

CERTIFICATE OF ASSAY

**B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS
METALLURGISTS 4**

TO Cyprus Anvil Mining Corporation

Certificate No. K-3149

Date September 12, 1980

I hereby certify that the following are the results of assays made by us upon the herein described DY core samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		Ounces Per Ton	g/tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent
61	1913 X		31	2.44	1.45	.03				
62	1914		4	.24	.72	.02				
63	1915		3	.12	.15	.01				
64	1916		9	.50	.53	.02				
65	1917		9	.09	.15	.03				
66	1918		14	.64	2.25	.07				
67	1919		8	.47	2.56	.04				
68	1920		27	1.74	3.39	.03				
69	1921		44	2.33	4.18	.04				
70	1922		37	2.70	3.46	.07				
71	1923 X		22	.99	2.33	.06				
72	1924		8	.16	.44	.06				
73	1925		17	.33	.51	.06				

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.


 Registered Assayer, Province of British Columbia

CYPRUS ANVIL MINING CORPORATION

Page 1 of 2

DDH 80-X-11

GEOCHEMICAL LOG

Kamloops Research and Assay Lab.

From	To	Int.	Samp. No.	Ag/AA GM/MT	Ag/Fa GM/MT	Pb %	Zn %	Pb+Zn %	S.G.	Cu %	BaO %	Au GMS/MT	Po %	Py %	Hg %	Mn %	Rec.	Und
612.9	613.4	0.5	1894	46.0	44.0	3.77	2.88	6.65	4.52	0.18	1.8	1.10	4.1	31.5	.001		0.5	4E8
613.4	615.5	2.1	1895	90.0	82.0	5.15	5.43	10.58	4.47	0.20	23.7	1.03	2.2	18.6	.003		2.0	4G0
615.5	616.2	0.7	1896	21.0		0.51	0.46			0.40							0.6	4E8
616.2	616.7	0.5	1897	2.0		0.05	0.04			0.01							0.4	4L1
616.7	618.1	1.4	1898	12.0		0.18	0.06			0.14							1.4	4C0
618.1	619.1	1.0	1899	11.0		0.11	0.06			0.13							0.9	4C0
623.8	624.1	0.3	1900	13.0		0.65	0.54			0.33							0.3	4G8
726.3	728.4	2.1	1901	4.0		0.12	0.20			0.02							2.1	4L7
728.4	729.6	1.2	1902	12.0		0.74	1.32			0.05							1.2	4L1
731.6	733.6	2.0	1903	29.0		2.02	2.40	4.42		0.04							2.0	4A4
733.6	735.6	2.0	1904	28.0		2.36	2.51	4.87		0.03							2.0	4A4
735.6	737.6	2.0	1905	30.0		2.21	4.85	7.06		0.03							2.0	4A4
737.6	739.8	2.2	1906	31.0		2.19	2.76	4.95		0.05							2.2	4A4
752.8	753.8	1.0	1907	9.0		0.33	0.72			0.10							0.9	4A0
753.8	757.5	3.7	1908	4.0		0.23	0.31			0.02							3.7	5B2
757.5	759.5	2.0	1909	4.0		0.29	0.17			0.03							2.0	4L7
759.5	761.5	2.0	1910	11.0		0.54	0.63			0.16							1.5	4L7
761.5	762.0	0.5	1911	2.0		0.04	0.09			0.03							0.5	4L7
767.3	768.4	1.1	1912	28.0		1.95	3.10	5.05		0.12							1.0	4L1
787.6	789.6	2.0	1913	31.0		2.44	1.45	3.89		0.03							2.0	4D0
789.6	790.0	0.4	1914	4.0		0.24	0.72			0.02							0.4	4D0
790.0	792.0	2.0	1915	3.0		0.12	0.15			0.01							2.0	4L1
792.0	794.0	2.0	1916	9.0		0.50	0.53			0.02							2.0	4L1
794.0	795.4	1.4	1917	9.0		0.09	0.15			0.03							1.4	4L1



KAMLOOPS RESEARCH & ASSAY LABORATORY LTD.

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS B.C.
V1S 1A7

PHONE: (604) 372-2784 — TELEX: 048-8320

CERTIFICATE OF ASSAY

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS
METALLURGISTS 5

TO Cyprus Anvil Mining Corporation


Certificate No. K-3428

Date December 19, 1980

I hereby certify that the following are the results of assays made by us upon the herein described _____ samples

Kral No.	Marked	GOLD	SILVER	Py	Po	BaO	Hg	S.G.		
		grams per tonne	grams per tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent
81	X 1874	1.10	99	9.4	1.3	31.6	.009	4.46		
82	1875	1.03	122	7.6	1.2	30.5	.008	4.38		
83	1876	2.06	112	29.0	2.9	1.9	.004	4.41		
84	1877	1.99	102	14.5	1.1	24.8	.006	4.40		
85	1878	1.65	46	28.9	1.5	7.1	.003	3.83		
86	1879	1.54	76	30.4	1.6	1.9	.006	5.38		
87	1880	1.37	80	19.7	.9	22.7	.006	4.54		
88	1881	1.65	70	28.0	2.0	2.7	.005	4.34		
89	1882	1.99	76	32.8	1.5	4.4	.005	4.60		
90	1883	1.44	42	10.4	2.4	2.6	.004	3.22		
91	1884	.51	26	7.4	.9	0.7	.003	2.82		
92	1885	1.10	98	25.1	2.1	4.3	.004	4.20		
93	1894	1.10	44	31.5	4.1	1.8	.001	4.52		
94	1895	1.03	82	18.6	2.2	23.7	.003	4.47		
95	1941	.58	64	13.5	4.3	29.3	.003	4.51		
96	1942	.86	48	19.8	7.3	18.8	.002	4.26		
97	1943	.58	46	19.4	3.7	22.3	.004	4.41		
98	1944	.58	46	9.5	2.0	0.9	.003	3.03		
99	2006	.69	108	13.1	2.0	3.2	.002	3.51		
100	2007	.58	50	17.2	3.4	0.6	.002	3.50		

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.


Registered Assayer, Province of British Columbia



KAMLOOPS RESEARCH & ASSAY LABORATORY LTD.

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS B.C.
V1S 1A7

PHONE: (604) 372-2784 — TELEX: 048-8320

CERTIFICATE OF ASSAY

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS
METALLURGISTS 2

TO Cyprus Anvil Mining Corporation

Certificate No. K-3279

Date October 8, 1980

I hereby certify that the following are the results of assays made by us upon the herein described _____ samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		Ounces Per Ton	Ounces Per Ton	Percent	Percent	Percént	Percent	Percent	Percent	Percent
X-13	21	1946 X		32	2.18	1.05	.14			
	22	1947		15	.95	1.65	.12			
	23	1948		41	3.05	3.64	.07			
	24	1949		56	3.35	6.12	.10			
	25	1950 X		48	3.45	4.86	.20			
	26	2001 X		25	1.64	2.86	.10			
	27	2002		15	1.05	2.38	.08			
28	2003		5	.19	.14	.05				
29	2004		37	2.01	2.64	.10				
30	2005		33	2.03	2.95	.08				
X-12	31	2006		103	8.0	8.77	.10			
	32	2007		47	2.42	9.03	.03			
	33	2008		18	1.21	1.69	.07			
	34	2009		34	2.15	2.48	.10			
	35	2010		7	.33	.55	.09			
	36	2011		17	.83	1.45	.09			
	37	2012		36	1.67	7.47	.10			
	38	2013		55	3.31	4.56	.13			
	39	2014		29	1.56	.69	.33			
	40	2015		2	.16	.07	.08			

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.

Registered Assayer, Province of British Columbia



KAMLOOPS RESEARCH & ASSAY LABORATORY LTD.

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS B.C.
V1S 1A7

PHONE: (604) 372-2784 — TELEX: 048-8320

CERTIFICATE OF ASSAY

**B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS
METALLURGISTS**

3

TO Cyprus Anvil Mining Corporation

Certificate No. K-3279

Date October 8, 1980

I hereby certify that the following are the results of assays made by us upon the herein described _____ samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		Ounces Per Ton	Ounces Per Ton	Percent	Percent	Percent	Percent	Percent	Percent	Percent
X-12	41		4	.33	.13	.11				
	42	2016 X		44	1.92	1.24	.33			
	43	2017		39	1.74	2.56	.26			
	44	2018		18	1.01	1.98	.12			
	45	2019		37	2.16	8.06	.08			
	46	2020		16	1.08	2.33	.08			
	47	2021		28	1.22	1.46	.07			
	48	2022		32	.70	.35	.14			
	49	2023		6	.15	.08	.05			
	50	2024		12	.45	.88	.06			
51	2025		14	.26	.16	.08				
52	2026		39	2.39	2.18	.23				
53	2027		43	3.28	2.64	.22				
54	2028		28	1.11	.77	.39				
55	2029		25	.41	.16	.22				
56	2030 X		14	.34	.20	.15				
57	2031		18	.62	.17	.27				
58	2032		2	.39	.19	.05				
59	2033		3	.18	.20	.03				
60	2034		4	.25	.29	.05				
	2035									

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.

Registered Assayer, Province of British Columbia



KAMLOOPS RESEARCH & ASSAY LABORATORY LTD.

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS B.C.
V1S 1A7

PHONE: (604) 372-2784 — TELEX: 048-8320

CERTIFICATE OF ASSAY

**B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS
METALLURGISTS 4**

TO Cyprus Anvil Mining Corporation

Certificate No. K-3279

Date October 8, 1980

I hereby certify that the following are the results of assays made by us upon the herein described _____ samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		Ounces Per Ton	Ounces Per Ton	Percent	Percent	Percent	Percent	Percent	Percent	Percent
X-12 61	2036 X		7	.43	.47	.05				
62	2037		3	.35	.67	.10				
63	2038		17	1.02	1.96	.11				
64	2039		5	.22	.49	.03				
65	2040 X		10	.22	.41	.01				
66	2041		10	.22	.14	.01				
67	2042		66	4.05	3.29	.09				
68	2096		2	.03	.11	.01				
69	2097		1	.01	.06	.01				
PELT 70	2098		TR	.03	.06	.02				
71	2099		TR	.02	.08	L.01				
72	2100		TR	.03	.07	L.01				
	<u>REPEATS</u>									
	1947		15	.95	1.66	.12				
	2021		15	1.05	2.23	.08				
	1942		47	3.37	4.33	.25				
	2011		18	.82	1.43	.09				
	2036		7	.43	.46	.05				

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.

Registered Assayer, Province of British Columbia



KAMLOOPS RESEARCH & ASSAY LABORATORY LTD.

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS B.C.
V1S 1A7

PHONE: (604) 372-2784 — TELEX: 048-8320

CERTIFICATE OF ASSAY

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS
METALLURGISTS 5

TO Cyprus Anvil Mining Corporation

Certificate No. K-3279

Date October 8, 1980

I hereby certify that the following are the results of assays made by us upon the herein described _____ samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		Ounces Per Ton	Ounces Per Ton	Percent	Percent	Percent	Percent	Percent	Percent	Percent
	<u>STANDARDS</u>									
	100		95	5.44	-	.108				
	200		84	4.99	6.73	.155				
	300		40	2.34	4.35	.040				
	MP1		60	1.95	-	2.12				
	RU1		11	-	2.25	.89				
	KC1		-	-	-	.112				
	PTC1		10	-	-	-				

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.

Registered Assayer, Province of British Columbia

DDH 80-X-12

GEOCHEMICAL LOG

Kamloops Research and Assay Lab.

From	To	Int.	Samp. No.	Ag/AA GM/MT	Ag/Fa GM/MT	Pb %	Zn %	Pb+Zn %	S.G.	Cu %	BaO %	Au GMS/MT	Po %	Py %	Hg %	Mn %	Unit
843.5	844.2	0.7	2003	5.0		0.19	0.14			0.05							4A1
844.2	846.0	1.8	2004	37.0		2.01	2.64	4.65		0.10							4A0
846.2	848.0	1.8	2005	33.0		2.03	2.95	4.98		0.08							4A0
848.0	848.7	0.7	2006	103.0	108.0	8.00	8.77	16.77	3.51	0.10	3.2	0.69	2.0	13.1	.002		4D0
848.7	849.3	0.6	2007	47.0	50.0	2.42	9.03	11.45	3.50	0.03	0.6	0.58	3.4	17.2	.002		4E0
849.9	851.9	2.0	2008	18.0		1.21	1.69	2.90		0.07							4A0
851.9	853.9	2.0	2009	34.0		2.15	2.48	4.63		0.10							4A0
853.9	855.9	2.0	2010	7.0		0.33	0.55	0.88		0.09							4A0
855.9	857.4	1.5	2011	17.0		0.83	1.45	2.28		0.09							4A0
857.4	858.1	0.7	2012	36.0		1.67	7.47	9.14		0.10							4E0
858.1	858.9	0.8	2013	55.0		3.31	4.56	7.87		0.13							4G4
858.9	859.2	0.3	2014	29.0		1.56	0.69	2.25		0.33							4E1
859.2	860.7	1.5	2015	2.0		0.16	0.07	0.23		0.08							4L3
860.7	861.5	0.8	2016	4.0		0.33	0.13	0.46		0.11							4L7
861.5	861.9	0.4	2017	44.0		1.92	1.24	3.16		0.33							4E6
861.9	863.8	1.9	2018	39.0		1.74	2.56	4.30		0.26							4K8
863.8	864.2	0.4	2019	18.0		1.01	1.98	2.99		0.12							4A0
864.2	865.2	1.0	2020	37.0		2.16	8.06	10.22		0.08							4E0
865.2	866.4	1.2	2021	16.0		1.08	2.33	3.41		0.08							4A0
868.6	870.8	2.2	2022	28.0		1.22	1.46	2.68		0.07							4A0
870.8	872.9	2.1	2023	32.0		0.70	0.35	1.05		0.14							4E0
872.9	874.9	2.0	2024	6.0		0.15	0.08	0.23		0.05							4A0
874.9	876.4	1.5	2025	12.0		0.45	0.88	1.33		0.06							4A0
876.4	877.1	0.7	2026	14.0		0.26	0.16	0.42		0.08							4E1
877.1	879.1	2.0	2027	39.0		2.39	2.18	4.57		0.23							4G0
879.1	881.1	2.0	2028	43.0		3.28	2.64	5.92		0.22							4G8
881.1	882.5	1.4	2029	28.0		1.11	0.77	1.88		0.39							4G8
882.5	883.0	0.5	2030	25.0		0.41	0.16	0.57		0.22							4C0
884.5	885.3	0.8	2031	14.0		0.34	0.20			0.15							4C8
885.3	886.1	0.8	2032	18.0		0.62	0.17			0.27							4C8

DDH 80-X-12

GEOCHEMICAL LOG

Kamloops Research and Assay Lab.

<u>From</u>	<u>To</u>	<u>Int.</u>	<u>Samp.</u> <u>No.</u>	<u>Ag/AA</u> <u>GM/MT</u>	<u>Ag/Fa</u> <u>GM/MT</u>	<u>Pb %</u>	<u>Zn %</u>	<u>Pb+Zn</u> <u>%</u>	<u>S.G.</u>	<u>Cu %</u>	<u>BaO %</u>	<u>Au</u> <u>GMS/MT</u>	<u>Po %</u>	<u>Py %</u>	<u>Hg %</u>	<u>Mn %</u>	<u>Unit</u>
886.4	888.4	2.0	2033	2.0		0.39	0.19			0.05							4L7
888.4	890.4	2.0	2034	3.0		0.18	0.20			0.03							4L7
890.4	892.4	2.0	2035	4.0		0.25	0.29			0.05							4L7
892.4	893.8	1.4	2036	7.0		0.43	0.47			0.05							4L7
897.6	899.6	2.0	2037	3.0		0.35	0.67			0.10							4A0
899.6	901.6	2.0	2038	17.0		1.02	1.96			0.11							4A0
901.6	902.4	0.8	2039	5.0		0.22	0.49			0.03							4A0
902.4	904.4	2.0	2040	10.0		0.22	0.41			0.01							4E0
904.4	906.7	2.3	2041	10.0		0.22	0.14			0.01							4E0
906.7	907.4	0.7	2042	66.0		4.05	3.29	7.34		0.09							4C7



KAMLOOPS RESEARCH & ASSAY LABORATORY LTD.

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS B.C.
V1S 1A7

PHONE: (604) 372-2784 — TELEX: 048-8320

CERTIFICATE OF ASSAY

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS
METALLURGISTS 5

TO Cyprus Anvil Mining Corporation


Certificate No. K-3428

Date December 19, 1980

I hereby certify that the following are the results of assays made by us upon the herein described _____ samples

Kral No.	Marked	GOLD	SILVER	Py	Po	BaO	Hg	S.G.		
		grams per tonne	grams per tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent
81	X 1874	1.10	99	9.4	1.3	31.6	.009	4.46		
82	1875	1.03	122	7.6	1.2	30.5	.008	4.38		
83	1876	2.06	112	29.0	2.9	1.9	.004	4.41		
84	1877	1.99	102	14.5	1.1	24.8	.006	4.40		
85	1878	1.65	46	28.9	1.5	7.1	.003	3.83		
86	1879	1.54	76	38.4	1.6	1.9	.006	5.38		
87	1880	1.37	80	19.7	.9	22.7	.006	4.54		
88	1881	1.65	70	28.0	2.0	2.7	.005	4.34		
10 89	1882	1.99	76	32.8	1.5	4.4	.005	4.60		
90	1883	1.44	42	10.4	2.4	2.6	.004	3.22		
91	1884	.51	26	7.4	.9	0.7	.003	2.82		
92	1885	1.10	98	25.1	2.1	4.3	.004	4.20		
11 93	1894	1.10	44	31.5	4.1	1.8	.001	4.52		
94	1895	1.03	82	18.6	2.2	23.7	.003	4.47		
95	1941	.58	64	13.5	4.3	29.3	.003	4.51		
96	1942	.86	48	19.8	7.3	18.8	.002	4.26		
13 97	1943	.58	46	19.4	3.7	22.3	.004	4.41		
98	1944	.58	46	9.5	2.0	0.9	.003	3.03		
99	2006	.69	108	13.1	2.0	3.2	.002	3.51		
12 100	2007	.58	50	17.2	3.4	0.6	.002	3.50		

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.


Registered Assayer, Province of British Columbia



Member
Canadian Testing
Association

KAMLOOPS RESEARCH & ASSAY LABORATORY LTD.

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS B.C.
V1S 1A7

PHONE: (604) 372-2784 — TELEX: 048-8320

CERTIFICATE OF ASSAY

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS
METALLURGISTS

TO Cyprus Anvil Mining Corporation

330 - 355 Burrard St.

Vancouver, B.C.

Certificate No. K-3279

Date October 8, 1980

I hereby certify that the following are the results of assays made by us upon the herein described _____ samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		Ounces Per Ton	Ounces Per Ton	Percent	Percent	Percent	Percent	Percent	Percent	Percent
X-13 1	1926 X		63	3.85	4.55	.37				
2	1927		9	.64	1.22	.08				
3	1928		36	2.10	2.59	.24				
4	1929		26	1.41	2.53	.36				
5	1930 X		33	1.66	2.19	.31				
6	1931		19	.78	.73	.19				
7	1932		24	1.60	2.75	.37				
8	1933		13	.82	2.01	.20				
9	1934		36	3.13	5.67	.21				
10	1935		29	1.86	1.15	.35				
11	1936		11	.55	1.44	.29				
12	1937		8	.38	.48	.15				
13	1938		6	.20	.18	.26				
14	1939		4	.07	.04	.17				
15	1940 X		4	.09	.05	.11				
16	1941		67	5.05	7.52	.14				
17	1942		49	3.46	4.38	.26				
18	1943		51	3.48	5.67	.30				
19	1944		44	3.55	3.84	.11				
20	1945		31	1.83	1.49	.14				

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.

Registered Assayer, Province of British Columbia



KAMLOOPS RESEARCH & ASSAY LABORATORY LTD.

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS B.C.
V1S 1A7

PHONE: (604) 372-2784 — TELEX: 048-8320

CERTIFICATE OF ASSAY

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS
METALLURGISTS 2

TO Cyprus Anvil Mining Corporation

Certificate No. K-3279

Date October 8, 1980

I hereby certify that the following are the results of assays made by us upon the herein described _____ samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		Ounces Per Ton	Ounces Per Ton	Percent	Percent	Percent	Percent	Percent	Percent	Percent
X-13 21 22 23 24 25 26 27	1946 X		32	2.18	1.05	.14				
	1947		15	.95	1.65	.12				
	1948		41	3.05	3.64	.07				
	1949		56	3.35	6.12	.10				
	1950 X		48	3.45	4.86	.20				
	2001 X		25	1.64	2.86	.10				
	2002		15	1.05	2.38	.08				
X-12 28 29 30 31 32 33 34 35 36 37 38 39 40	2003		5	.19	.14	.05				
	2004		37	2.01	2.64	.10				
	2005		33	2.03	2.95	.08				
	2006		103	8.0	8.77	.10				
	2007		47	2.42	9.03	.03				
	2008		18	1.21	1.69	.07				
	2009		34	2.15	2.48	.10				
	2010		7	.33	.55	.09				
	2011		17	.83	1.45	.09				
	2012		36	1.67	7.47	.10				
	2013		55	3.31	4.56	.13				
	2014		29	1.56	.69	.33				
	2015		2	.16	.07	.08				

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.

Registered Assayer, Province of British Columbia



Member
Canadian Testing
Association

KAMLOOPS RESEARCH & ASSAY LABORATORY LTD.

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS B.C.
V1S 1A7

PHONE: (604) 372-2784 — TELEX: 048-8320

CERTIFICATE OF ASSAY

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS
METALLURGISTS

TO Cyprus Anvil Mining Corporation
330 - 355 Burrard Street
Vancouver, B.C. V6C 2G8


Certificate No. K-3035

Date January 21, 1981

I hereby certify that the following are the results of assays made by us upon the herein described _____ samples

Kral No	Marked	GOLD	SILVER	Pb	Zn	Cu				
		Ounces Per Ton	grams per tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent
1	1809		15	.36	.39	.52				

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.


Registered Assayer, Province of British Columbia



Member
Canadian Testing
Association

KAMLOOPS RESEARCH & ASSAY LABORATORY LTD.

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS B.C.
V1S 1A7

PHONE: (604) 372-2784 — TELEX: 048-8320

CERTIFICATE OF ASSAY

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS
METALLURGISTS

1980 D1

TO Cyprus Anvil Mining Corporation
330 - 355 Burrard St.
Vancouver, B.C. V6C 2G8

Certificate No. K-3428

Date December 18, 1980

I hereby certify that the following are the results of assays made by us upon the herein described _____ samples

Kral No.	Marked	GOLD	SILVER	Py	Po	BaO	Hg	S.G.		
		grams per tonne	grams per tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent
1	X 1505	1.70	90	19.4	1.9	10.0	.006	4.51		
2	1506	1.17	106	13.0	1.1	26.5	.008	4.46		
3	1507	.82	108	15.6	2.3	22.3	.009	4.47		
4	1508	.27	40	2.6	1.2	2.3	.005	2.80		
5	1509	.34	38	2.4	.8	0.6	.005	2.72		
6	1540	1.51	82	19.7	.5	24.5	.007	4.27		
X-02 7	1541	1.37	98	23.7	1.5	1.7	.009	4.20		
8	1542	.75	78	18.5	3.0	27.2	.008	4.55		
9	1543	1.92	58	30.7	1.2	8.0	.010	4.58		
10	1547	.69	68	13.4	3.0	17.3	.005	3.88		
11	1548	1.70	100	17.1	3.3	3.1	.006	3.66		
12	1560	1.37	118	16.6	1.5	22.0	.005	5.21		
X-04 13	1561	2.09	19	34.7	7.8	.1	.002	4.57		
14	1562	1.37	113	9.3	.8	33.7	.009	4.42		
15	1651	1.23	63	15.2	2.5	9.3	.009	3.58		
16	1652	1.23	29	26.0	3.5	9.3	.005	4.36		
17	1653	.69	120	10.2	2.8	31.0	.010	4.44		
18	1654	.62	119	11.5	3.8	26.9	.009	4.65		
05 19	1655	.93	106	23.9	4.1	12.6	.007	4.85		
20	1656	.62	78	20.7	.9	21.9	.009	4.44		

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.



Registered Assayer, Province of British Columbia



Member
Canadian Testing
Association

KAMLOOPS RESEARCH & ASSAY LABORATORY LTD.

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS B.C.

V1S 1A7

PHONE: (604) 372-2784 — TELEX: 048-8320

CERTIFICATE OF ASSAY

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS
METALLURGISTS 2

TO Cyprus Anvil Mining Corporation

Certificate No. K-3428

Date December 18, 1980

I hereby certify that the following are the results of assays made by us upon the herein described _____ samples

Kral No.	Marked	GOLD	SILVER	Py	Po	BaO	Hg	S.G.		
		grams per tonne	grams per tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent
21	X 1657	1.17	102	19.4	1.7	19.1	.007	4.49		
22	1658	1.10	85	12.4	.6	34.8	.007	4.53		
23	1659	.82	87	15.2	1.0	29.2	.009	4.68		
24	1667	2.16	66	24.0	1.8	12.1	.007	4.36		
25	1668	1.30	54	30.3	7.8	1.5	.005	4.42		
26	1669	1.23	59	27.8	2.6	1.9	.005	4.15		
27	1693	.55	59	16.3	4.3	22.0	.004	4.19		
28	1694	.62	64	20.5	2.6	21.9	.004	4.86		
29	1701	1.47	89	18.2	2.8	13.3	.006	4.35		
30	1702	1.71	45	28.7	11.8	1.9	.003	4.83		
31	1703	1.09	84	15.2	2.3	28.2	.007	4.55		
32	1711	1.65	116	17.2	17.2	0.08	.005	4.46		
33	1712	1.78	50	25.8	12.9	0.06	.003	4.42		
34	1713	1.17	99	16.9	9.4	10.7	.005	3.94		
35	1722	.69	32	15.8	7.8	5.3	.006	4.12		
36	1723	.82	35	16.5	11.3	0.9	.003	3.69		
37	1744	.82	84	19.4	3.1	16.8	.005	4.38		
38	1749	.62	53	13.5	1.5	0.17	.004	3.30		
39	1750	.69	33	30.9	.8	3.1	.007	4.58		
40	1751	.75	50	16.6	5.1	26.6	.005	4.46		

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.

Registered Assayer, Province of British Columbia



Member
Canadian Testing
Association

KAMLOOPS RESEARCH & ASSAY LABORATORY LTD.

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS B.C.

V1S 1A7

PHONE: (604) 372-2784 — TELEX: 048-8320

CERTIFICATE OF ASSAY

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS
METALLURGISTS 3

TO Cyprus Anvil Mining Corporation

Certificate No. K-3428

Date December 18, 1980

I hereby certify that the following are the results of assays made by us upon the herein described _____ samples

Kral No.	Marked	GOLD	SILVER	Py	Po	BaO	Hg	S.G.		
		grams per tonne	grams per tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent
07	X 1752	.96	52	16.1	4.9	17.5	.004	4.13		
	1753	.75	51	24.0	1.0	0.9	.004	3.78		
	1754	.69	38	10.0	1.5	0.2	.003	3.22>	*
	1766	1.51	75	24.1	1.6	14.3	.006	3.90		
	1767	.69	64	18.7	1.8	14.8	.006	4.43		
	1768	.93	83	24.2	1.7	6.5	.006	4.29		
	1769	.75	9	16.2	4.3	0.7	.002	3.10		
	1770	1.17	108	16.2	1.4	24.4	.007	4.35		
	1771	.82	106	17.0	4.2	20.9	.006	4.54		
	1772	1.47	24	34.4	9.5	0.1	.003	4.28		
08	1773	.75	17	17.5	7.3	1.3	.002	3.62		
	1774	.99	90	18.8	1.5	11.0	.008	4.23		
	1775	2.84	140	31.7	.6	6.5	.007	5.10		
	1776	1.37	73	36.0	.4	0.4	.006	4.63		
	1777	.55	99	11.5	1.1	31.6	.007	4.51		
	1778	.75	138	10.8	2.1	25.6	.008	4.75		
	1779	1.16	77	21.6	1.0	13.3	.007	4.27		
	1785	.69	109	15.7	1.4	22.2	.007	4.45		
	1786	1.71	51	28.2	6.5	2.0	.004	4.50		
	1787	.69	83	14.8	6.4	15.7	.004	4.25		→

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.


Registered Assayer, Province of British Columbia



KAMLOOPS RESEARCH & ASSAY LABORATORY LTD.

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS B.C.
V1S 1A7

PHONE: (604) 372-2784 — TELEX: 048-8320

CERTIFICATE OF ASSAY

**B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS
METALLURGISTS**

4

TO Cyprus Anvil Mining Corporation

Certificate No. K-3428

Date December 19, 1980

I hereby certify that the following are the results of assays made by us upon the herein described _____ samples

Kral No.	Marked	GOLD	SILVER	Py	Po	BaO	Hg	S.G.		
		grams per tonne	grams per tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent
08	X 1788	1.54	49	28.2	4.3	0.6	.003	4.15		
	1789	1.30	51	28.9	6.0	0.1	.004	3.86		
	1790	1.51	82	17.6	4.6	0.1	.006	4.39		
64	1839	.34	83	9.9	9.8	1.3	.003	3.45		
65	1840	.27	109	2.3	31.0	0.1	.003	3.89		
66	1841	1.17	83	7.9	8.7	1.5	.003	3.39		
67	1842	1.10	124	12.3	13.0	2.4	.002	4.15		
68	1843	.96	110	11.7	12.2	3.3	.002	4.12		
69	1844	.75	97	13.3	8.0	7.5	.002	4.15		
70	1845	.69	74	12.4	7.1	7.6	.003	3.74		
09	1846	.96	133	12.9	7.3	10.2	.003	3.94		
	1847	1.51	122	12.2	13.5	3.9	.003	4.27		
	1848	1.85	60	25.0	12.1	10.1	.002	4.33		
	1851	1.78	103	14.4	10.1	9.6	.004	4.38		
	1852	.34	136	10.4	13.6	6.7	.002	4.04		
76	1869	.96	88	15.0	1.4	21.0	.007	4.29		
77	1870	1.78	75	28.5	1.8	3.5	.005	4.31		
78	1871	1.03	116	7.9	1.1	30.8	.009	4.43		
10	1872	1.34	78	15.4	2.7	10.9	.005	4.14		
	1873	1.78	105	15.0	2.2	15.9	.007	4.30		

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.

Registered Assayer, Province of British Columbia



KAMLOOPS RESEARCH & ASSAY LABORATORY LTD.

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS B.C.
V1S 1A7

PHONE: (604) 372-2784 — TELEX: 048-8320

CERTIFICATE OF ASSAY

**B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS
METALLURGISTS** 5

TO Cyprus Anvil Mining Corporation


Certificate No. K-3428

Date December 19, 1980

I hereby certify that the following are the results of assays made by us upon the herein described _____ samples

Kral No.	Marked	GOLD	SILVER	Py	Po	BaO	Hg	S.G.		
		grams per tonne	grams per tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent
81	X 1874	1.10	99	9.4	1.3	31.6	.009	4.46		
82	1875	1.03	122	7.6	1.2	30.5	.008	4.38		
83	1876	2.06	112	29.0	2.9	1.9	.004	4.41		
84	1877	1.99	102	14.5	1.1	24.8	.006	4.40		
85	1878	1.65	46	28.9	1.5	7.1	.003	3.83		
86	1879	1.54	76	30.4	1.6	1.9	.006	5.38		
87	1880	1.37	80	19.7	.9	22.7	.006	4.54		
88	1881	1.65	70	28.0	2.0	2.7	.005	4.34		
89	1882	1.99	76	32.8	1.5	4.4	.005	4.60		
90	1883	1.44	42	10.4	2.4	2.6	.004	3.22		
91	1884	.51	26	7.4	.9	0.7	.003	2.82		
92	1885	1.10	98	25.1	2.1	4.3	.004	4.20		
93	1894	1.10	44	31.5	4.1	1.8	.001	4.52		
94	1895	1.03	82	18.6	2.2	23.7	.003	4.47		
95	1941	.58	64	13.5	4.3	29.3	.003	4.51		
96	1942	.86	48	19.8	7.3	18.8	.002	4.26		
97	1943	.58	46	19.4	3.7	22.3	.004	4.41		
98	1944	.58	46	9.5	2.0	0.9	.003	3.03		
99	2006	.69	108	13.1	2.0	3.2	.002	3.51		
100	2007	.58	50	17.2	3.4	0.6	.002	3.50		

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.


 Registered Assayer, Province of British Columbia



KAMLOOPS RESEARCH & ASSAY LABORATORY LTD.

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS B.C.
V1S 1A7

PHONE: (604) 372-2784 — TELEX: 048-8320

CERTIFICATE OF ASSAY

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS
METALLURGISTS 6

TO Cyprus Anvil Mining Corporation

Certificate No. K-3428

Date December 19, 1980

I hereby certify that the following are the results of assays made by us upon the herein described _____ samples

Kral No.	Marked	GOLD	SILVER	Py	Po	BaO	Hg	S.G.		
		grams per tonne	grams per tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent
101	X 3530	1.10	102	13.6	1.4	28.9	.006	4.46		
102	3531	1.37	50	26.4	6.3	6.2	.002	4.39		
103	3532	1.10	76	15.6	13.3	9.2	.003	4.18		
01 104	3536	1.17	62	13.8	.9	15.8	.005	3.76		
105	3537	.93	42	27.3	1.9	3.3	.002	4.02		
106	3538	.82	64	12.3	1.6	17.2	.006	3.78		
107	5147	.62	115	12.8	2.6	14.6	.004	3.92		
108	5148	.30	20	4.0	3.8	2.1	.001	2.79		
07 109	5149	.96	65	20.4	3.6	13.8	.004	4.45		
110	X 5150	2.54	36	30.5	8.5	0.1	.001	4.22		

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.

Registered Assayer, Province of British Columbia



KAMLOOPS RESEARCH & ASSAY LABORATORY LTD.

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS B.C.
V1S 1A7

PHONE: (604) 372-2784 — TELEX: 048-8320

CERTIFICATE OF ASSAY

**B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS
METALLURGISTS**

TO Cyprus Anvil Mining Corporation
330 - 355 Burrard St.
Vancouver, B.C.

Certificate No. K-3279

Date October 8, 1980

I hereby certify that the following are the results of assays made by us upon the herein described _____ samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		Ounces Per Ton	Ounces Per Ton	Percent	Percent	Percent	Percent	Percent	Percent	Percent
1	1926 X		63	3.85	4.55	.37				
2	1927		9	.64	1.22	.08				
3	1928		36	2.10	2.59	.24				
4	1929		26	1.41	2.53	.36				
5	1930 X		33	1.66	2.19	.31				
6	1931		19	.78	.73	.19				
7	1932		24	1.60	2.75	.37				
8	1933		13	.82	2.01	.20				
9	1934		36	3.13	5.67	.21				
10	1935		29	1.86	1.15	.35				
11	1936		11	.55	1.44	.29				
12	1937		8	.38	.48	.15				
13	1938		6	.20	.18	.26				
14	1939		4	.07	.04	.17				
15	1940 X		4	.09	.05	.11				
16	1941		67	5.05	7.52	.14				
17	1942		49	3.46	4.38	.26				
18	1943		51	3.48	5.67	.30				
19	1944		44	3.55	3.84	.11				
20	1945		31	1.83	1.49	.14				

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.

Registered Assayer, Province of British Columbia



KAMLOOPS RESEARCH & ASSAY LABORATORY LTD.

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS B.C.
V1S 1A7

PHONE: (604) 372-2784 — TELEX: 048-8320

CERTIFICATE OF ASSAY

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS
METALLURGISTS 2

TO Cyprus Anvil Mining Corporation

Certificate No. K-3279

Date October 8, 1980

I hereby certify that the following are the results of assays made by us upon the herein described _____ samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		Ounces Per Ton	Ounces Per Ton	Percent	Percent	Percent	Percent	Percent	Percent	Percent
21	1946 X		32	2.18	1.05	.14				
22	1947		15	.95	1.65	.12				
23	1948		41	3.05	3.64	.07				
24	1949		56	3.35	6.12	.10				
25	1950 X		48	3.45	4.86	.20				
26	2001 X		25	1.64	2.86	.10				
27	2002		15	1.05	2.38	.08				
28	2003		5	.19	.14	.05				
29	2004		37	2.01	2.64	.10				
30	2005		33	2.03	2.95	.08				
31	2006		103	8.0	8.77	.10				
32	2007		47	2.42	9.03	.03				
33	2008		18	1.21	1.69	.07				
34	2009		34	2.15	2.48	.10				
35	2010		7	.33	.55	.09				
36	2011		17	.83	1.45	.09				
37	2012		36	1.67	7.47	.10				
38	2013		55	3.31	4.56	.13				
39	2014		29	1.56	.69	.33				
40	2015		2	.16	.07	.08				

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.

Registered Assayer, Province of British Columbia



KAMLOOPS RESEARCH & ASSAY LABORATORY LTD.

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS B.C.
V1S 1A7

PHONE: (604) 372-2784 — TELEX: 048-8320

CERTIFICATE OF ASSAY

**B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS
METALLURGISTS**

3

TO Cyprus Anvil Mining Corporation

Certificate No. K-3279

Date October 8, 1980

I hereby certify that the following are the results of assays made by us upon the herein described _____ samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		Ounces Per Ton	Ounces Per Ton	Percent	Percent	Percent	Percent	Percent	Percent	Percent
41	2016 X		4	.33	.13	.11				
42	2017		44	1.92	1.24	.33				
43	2018		39	1.74	2.56	.26				
44	2019		18	1.01	1.98	.12				
45	2020		37	2.16	8.06	.08				
46	2021		16	1.08	2.33	.08				
47	2022		28	1.22	1.46	.07				
48	2023		32	.70	.35	.14				
49	2024		6	.15	.08	.05				
50	2025		12	.45	.88	.06				
51	2026		14	.26	.16	.08				
52	2027		39	2.39	2.18	.23				
53	2028		43	3.28	2.64	.22				
54	2029		28	1.11	.77	.39				
55	2030 X		25	.41	.16	.22				
56	2031		14	.34	.20	.15				
57	2032		18	.62	.17	.27				
58	2033		2	.39	.19	.05				
59	2034		3	.18	.20	.03				
60	2035		4	.25	.29	.05				

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.

Registered Assayer, Province of British Columbia



KAMLOOPS RESEARCH & ASSAY LABORATORY LTD.

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS B.C.

V1S 1A7

PHONE: (604) 372-2784 — TELEX: 048-8320

CERTIFICATE OF ASSAY

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS
METALLURGISTS 4

TO Cyprus Anvil Mining Corporation

Certificate No. K-3279

Date October 8, 1980

I hereby certify that the following are the results of assays made by us upon the herein described _____ samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		Ounces Per Ton	Ounces Per Ton	Percent	Percent	Percent	Percent	Percent	Percent	Percent
61	2036 X		7	.43	.47	.05				
62	2037		3	.35	.67	.10				
63	2038		17	1.02	1.96	.11				
64	2039		5	.22	.49	.03				
65	2040 X		10	.22	.41	.01				
66	2041		10	.22	.14	.01				
67	2042		66	4.05	3.29	.09				
68	2096		2	.03	.11	.01				
69	2097		1	.01	.06	.01				
70	2098		TR	.03	.06	.02				
71	2099		TR	.02	.08	L.01				
72	2100		TR	.03	.07	L.01				
	<u>REPEATS</u>									
	1947		15	.95	1.66	.12				
	2021		15	1.05	2.23	.08				
	1942		47	3.37	4.53	.25				
	2011		18	.82	1.43	.09				
	2036		7	.43	.46	.05				

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.

Registered Assayer, Province of British Columbia



KAMLOOPS RESEARCH & ASSAY LABORATORY LTD.

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS B.C.
V1S 1A7

PHONE: (604) 372-2784 — TELEX: 048-8320

CERTIFICATE OF ASSAY

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS
METALLURGISTS 5

TO Cyprus Anvil Mining Corporation

Certificate No. K-3279

Date October 8, 1980

I hereby certify that the following are the results of assays made by us upon the herein described _____ samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		Ounces Per Ton	Ounces Per Ton	Percent	Percent	Percent	Percent	Percent	Percent	Percent
	<u>STANDARDS</u>									
	100		95	5.44	-	.108				
	200		84	4.99	6.73	.155				
	300		40	2.34	4.35	.040				
	MP1		60	1.95	-	2.12				
	RU1		11	-	2.25	.89				
	KC1		-	-	-	.112				
	PTC1		10	-	-	-				

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.

Registered Assayer, Province of British Columbia



KAMLOOPS RESEARCH & ASSAY LABORATORY LTD.

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS B.C.
V1S 1A7

PHONE: (604) 372-2784 — TELEX: 048-8320

CERTIFICATE OF ASSAY

**B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS
METALLURGISTS**

TO Cyprus Anvil Mining Corporation
330 - 355 Burrard St.
Vancouver, B.C.

Certificate No. K-3149

Date September 12, 1980

I hereby certify that the following are the results of assays made by us upon the herein described DY core samples

Kral No	Marked	GOLD	SILVER	Pb	Zn	Cu				
		Ounces Per Ton	g/tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent
1	1853 X		21	1.72	1.21	.11				
2	1854		9	.56	.71	.09				
3	1855		4	.25	.30	.02				
4	1856		25	.19	2.80	.20				
5	1857		63	3.24	3.95	.35				
6	1858		4	.03	.05	.15				
7	1859		5	.26	.21	.15				
8	1860		5	.03	.06	.10				
9	1861		1	.04	.11	.10				
10	1862		2	.03	.07	.15				
11	1863 X		3	.02	.06	.14				
12	1864		6	.05	.11	.11				
13	1865		5	.07	.12	.07				
14	1866		5	.10	.14	.06				
15	1867		27	2.31	3.19	.06				
16	1868		46	3.67	5.75	.05				
17	1869		78	6.20	6.74	.07				
18	1870		73	3.90	4.66	.09				
19	1871		115	7.80	7.92	.11				
20	1872		113	6.10	4.83	.21				

NOTE:
Rejects retained three weeks.
Pulps retained three months.
unless otherwise arranged.

Registered Assayer, Province of British Columbia



KAMLOOPS RESEARCH & ASSAY LABORATORY LTD.

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS B.C.
V1S 1A7

PHONE: (604) 372-2784 — TELEX: 048-8320

CERTIFICATE OF ASSAY

**B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS
METALLURGISTS 2**

TO Cyprus Anvil Mining Corporation

Certificate No. K-3149

Date September 12, 1980

I hereby certify that the following are the results of assays made by us upon the herein described DY core samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		Ounces Per Ton	g/tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent
21	1873 X		140	7.20	7.46	.25				
22	1874		121	7.10	10.40	.14				
23	1875		121	6.60	10.70	.15				
24	1876		116	4.90	4.04	.27				
25	1877		103	6.80	8.71	.21				
26	1878		40	2.47	3.84	.22				
27	1879		66	4.87	7.10	.16				
28	1880		73	4.98	7.70	.13				
29	1881		65	4.38	6.35	.29				
30	1882		68	3.47	4.81	.29				
31	1883 X		42	2.87	5.55	.14				
32	1884		25	2.09	4.01	.02				
33	1885		99	3.22	5.18	.20				
34	1886		15	.14	.08	.33				
35	1887		12	.59	1.42	.04				
36	1888		13	.84	.84	.02				
37	1889		30	1.82	3.07	.12				
38	1890		32	1.91	2.11	.32				
39	1891		12	.84	2.05	.05				
40	1892		31	2.59	6.46	.03				

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.

Registered Assayer, Province of British Columbia



Member
Canadian Testing
Association

KAMLOOPS RESEARCH & ASSAY LABORATORY LTD.

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS B.C.

VIS 1A7

PHONE: (604) 372-2784 — TELEX: 048-8320

CERTIFICATE OF ASSAY

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS
METALLURGISTS 3

TO Cyprus Anvil Mining Corporation

Certificate No. K-3149

Date September 12, 1980

I hereby certify that the following are the results of assays made by us upon the herein described DY core samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		Ounces Per Ton	g/tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent
X-10 41	1893 X		24	1.99	3.55	.09				
42	1894		46	3.77	2.88	.18				
43	1895		90	5.15	5.43	.20				
44	1896		21	.51	.46	.40				
45	1897		2	.05	.04	.01				
46	1898		12	.18	.06	.14				
47	1899		11	.11	.06	.13				
48	1900		13	.65	.54	.33				
49	1901		4	.12	.20	.02				
X-11 50	1902		12	.74	1.32	.05				
51	1903 X		29	2.02	2.40	.04				
52	1904		28	2.36	2.51	.03				
53	1905		30	2.21	4.85	.03				
54	1906		31	2.19	2.76	.05				
55	1907		9	.33	.72	.10				
56	1908		4	.23	.31	.02				
57	1909		4	.29	.17	.03				
58	1910		11	.54	.63	.16				
59	1911		2	.04	.09	.03				
60	1912		28	1.95	3.10	.12				

NOTE:

Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.

Registered Assayer, Province of British Columbia



Member
Canadian Testing
Association

KAMLOOPS RESEARCH & ASSAY LABORATORY LTD.

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS B.C.
V1S 1A7

PHONE: (604) 372-2784 — TELEX: 048-8320

CERTIFICATE OF ASSAY

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS
METALLURGISTS 4

TO Cyprus Anvil Mining Corporation

Certificate No. K-3149

Date September 12, 1980

I hereby certify that the following are the results of assays made by us upon the herein described DY core samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		Ounces Per Ton	g/tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent
61	1913 X		31	2.44	1.45	.03				
62	1914		4	.24	.72	.02				
63	1915		3	.12	.15	.01				
64	1916		9	.50	.53	.02				
65	1917		9	.09	.15	.03				
66	1918		14	.64	2.25	.07				
67	1919		8	.47	2.56	.04				
68	1920		27	1.74	3.39	.03				
69	1921		44	2.33	4.18	.04				
70	1922		37	2.70	3.46	.07				
71	1923 X		22	.99	2.33	.06				
72	1924		8	.16	.44	.06				
73	1925		17	.33	.51	.06				

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.

Registered Assayer, Province of British Columbia



Member
Canadian Testing
Association

KAMLOOPS RESEARCH & ASSAY LABORATORY LTD.

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS B.C.

V1S 1A7

PHONE: (604) 372-2784 — TELEX: 048-8320

CERTIFICATE OF ASSAY

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS
METALLURGISTS

TO Cyprus Anvil Mining Corporation

330 - 355 Burrard St.

Vancouver, B.C. V6C 2G8

Attention: Mr. Darryl Hanson

Certificate No. K-3049

Date August 21, 1980

I hereby certify that the following are the results of assays made by us upon the herein described DY core samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		g/tonne	g/tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent
1	X 1786	-	46	3.15	3.39	.34				
2	1787	-	94	5.42	8.20	.11				
3	1788	-	43	2.39	2.32	.33				
4	1789	-	50	4.18	3.87	.40				
5	1790	-	89	7.69	8.50	.18				
6	1791	-	19	.72	.77	.26				
7	1792	.446	22	1.12	1.22	.32				
8	1793	1.029	31	1.28	1.72	.33				
9	1794	.377	147	8.14	8.52	.09				
10	1795	.514	42	2.60	3.60	.15				
11	X 1796	.651	38	2.69	1.58	.18				
12	1797	.137	42	3.03	3.74	.05				
13	1798	.309	95	6.13	10.00	.13				
14	1799	.137	30	1.64	1.44	.14				
15	1800	.274	10	.35	.17	.09				
16	1811	.480	11	.22	.19	.33				
17	1812	.549	12	.18	.25	.28				
18	1813	.789	16	.29	.18	.29				
19	1814	.583	15	.15	.13	.31				
20	1815	-	15	.63	.08	.21				

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.

Registered Assayer, Province of British Columbia



Member
Canadian Testing
Association

KAMLOOPS RESEARCH & ASSAY LABORATORY LTD.

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS B.C.

V1S 1A7

PHONE: (604) 372-2784 — TELEX: 048-8320

CERTIFICATE OF ASSAY

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS
METALLURGISTS 2

TO Cyprus Anvil Mining Corporation

Certificate No. K-3049

Date August 21, 1980

I hereby certify that the following are the results of assays made by us upon the herein described DY core samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		g/tonne	g/tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent
X-08	X 1816		11	.28	.10	.33				
	1817		12	.45	.37	.26				
	1818		7	.13	.13	.24				
	1819		5	.09	.07	.08				
	1820		5	.03	.06	.07				
	1821		4	.05	.03	.05				
	1822		4	.02	.02	.04				
	1823		17	.84	1.07	.07				
	1824		16	.83	1.46	.07				
	1825		90	.61	6.98	.22				
31	X 1826		20	.28	.76	.48				
X-09	1827		22	.45	.60	.21				
	1828		12	.82	.45	.08				
	1829		28	1.82	2.54	.22				
	1830		20	.88	1.40	.16				
	1831		54	3.48	3.80	.24				
	1832		11	.42	.25	.16				
	1833		56	3.42	3.05	.32				
	1834		2	.05	.02	.02				
	1835		15	.76	.89	.10				

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.

Registered Assayer, Province of British Columbia



KAMLOOPS RESEARCH & ASSAY LABORATORY LTD.

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS B.C.

V1S 1A7

PHONE: (604) 372-2784 — TELEX: 048-8320

CERTIFICATE OF ASSAY

**B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS
METALLURGISTS 3**

TO Cyprus Anvil Mining Corporation

Certificate No. K-3049

Date August 21, 1980

I hereby certify that the following are the results of assays made by us upon the herein described DY core samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		g/tonne	g/tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent
X-09	X 1836		3	.11	.10	.02				
	1837		25	1.68	1.75	.39				
	1838		20	1.37	1.25	.28				
	1839		96	6.58	5.06	.20				
	1840		129	9.37	4.68	.13				
	1841		90	7.40	4.11	.06				
	1842		158	11.78	5.63	.11				
	1843		130	11.69	5.31	.10				
	1844		110	9.77	5.29	.03				
	1845		80	6.45	6.53	.05				
51	X 1846		185	11.28	4.47	.09				
52	1847		145	11.38	4.94	.16				
53	1848		64	4.34	2.29	.34				
54	1849		31	1.59	1.15	.63				
55	1850		27	.98	1.08	.11				
56	1851		176	9.12	5.94	.13				
57	1852		164	10.71	7.22	.09				

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.

[Signature]
Registered Assayer, Province of British Columbia



Member
Canadian Testing
Association

KAMLOOPS RESEARCH & ASSAY LABORATORY LTD.

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS B.C.

V1S 1A7

PHONE: (604) 372-2784 — TELEX: 048-8320

CERTIFICATE OF ASSAY

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS
METALLURGISTS 4

TO Cyprus Anvil Mining Corporation


Certificate No. K-3049

Date August 21, 1980

I hereby certify that the following are the results of assays made by us upon the herein described DY core samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		g/tonne	g/tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent
1	1801	.514 -								
2	1802	1.646 -								
3	1803	.823 -								
4	1804	.617 -								
5	1805	.686 -								
6	1806	.480 -								
7	1807	.309 -								
8	1808	.652 -								
9	1809	.514 -								
10	1810	.549 -								
	<u>Repeats</u>									
	1795									
	1815		42	2.59	3.63	.15				
	1839		15	.61	.08	.21				
	1847		90	6.40	4.85	.19				
			140	11.15	4.76	.15				

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.


Registered Assayer, Province of British Columbia



KAMLOOPS RESEARCH & ASSAY LABORATORY LTD.

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS B.C.
V1S 1A7

PHONE: (604) 372-2784 — TELEX: 048-8320

CERTIFICATE OF ASSAY

**B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS
METALLURGISTS 5**

TO Cyprus Anvil Mining Corporation

Certificate No. K-3049

Date August 21, 1980

I hereby certify that the following are the results of assays made by us upon the herein described DY core samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		g/tonne	g/tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent
	<u>Standards</u>									
	100		97	5.70	8.93	.10				
	200		82	4.97	6.67	.15				
	300		40	2.13	4.39	.04				
	MP-1		58	1.79	-	-				
	PTC-1		7	-	-	-				
	KC-1		1133	6.94	-	.12				

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.

cc Dr. G. Simpson

Registered Assayer, Province of British Columbia



KAMLOOPS RESEARCH & ASSAY LABORATORY LTD.

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS B.C.
V1S 1A7

PHONE: (604) 372-2784 — TELEX: 048-8320

CERTIFICATE OF ASSAY

**B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS
METALLURGISTS**

TO Cyprus Anvil Mining Corporation

330 - 355 Burrard St.

Vancouver, B.C. V2C 2G8

Attention: Dr. G. Simpson

Certificate No. K-2775

Date May 28, 1980

I hereby certify that the following are the results of assays made by us upon the herein described drill core samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		Ounces Per Ton	g/tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent
X-03 1	1553		45	2.38	3.44	.17				
2	1554		20	.98	.50	.49				
3	1555		46	3.75	2.72	.05				
4	1556		37	1.85	2.76	.32				
5	1557		24	1.52	1.46	.07				
X-04 6	1559		52	.90	.97	.14				
7	1560		135	7.38	9.30	.20				
8	1561		16	.56	.49	.43				
9	1562		127	7.19	9.52	.05				
10	1563		1	.04	.04	.12				
11	1564		1	.17	.09	.14				
12	1565		1	.39	.24	.10				
13	1566		1	.03	.04	.07				
14	1567		1	.02	.02	.04				
15	1568		1	.02	.02	.06				
16	1569		5	.22	.08	.10				
17	1570		10	.72	.94	.05				
18	1571		36	1.39	1.32	.15				
19	1572		40	2.75	1.92	.31				
20	1573		43	2.72	3.95	.04				

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.

JAB for PJB
Registered Assayer, Province of British Columbia



KAMLOOPS RESEARCH & ASSAY LABORATORY LTD.

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS B.C.
V1S 1A7

PHONE: (604) 372-2784 — TELEX: 048-8320.

CERTIFICATE OF ASSAY

**B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS
METALLURGISTS 2**

TO Cyprus Anvil Mining Corporation

Certificate No. K-2775

Date May 28, 1980

I hereby certify that the following are the results of assays made by us upon the herein described drill core samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		Ounces Per Ton	g/tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent
21	1574		78	6.04	6.35	.06				
22	1575		8	.50	1.29	.12				
23	1576		7	.27	.41	.26				
24	1577		22	1.49	1.33	.16				
25	1578		14	1.09	.98	.14				
	<u>Repeats</u>									
	1557		24	1.46	1.45	.07				
	1568		1	.02	.02	.06				
	<u>Standards</u>									
	100		95	5.43	8.73	.11				
	200		82	4.89	6.59	.15				
	300		40	2.29	4.37	.04				
	MP-1		58	1.88	15.75	2.08				
	RU-1		7	-	2.17	.85				

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.

cc Mr. Darryl Hanson

Darryl Hanson

Registered Assayer, Province of British Columbia



Kamloops Research & Assay Laboratory Ltd.

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS, B.C. V1S 1A7
TELEPHONE 372-2784 TELEX 048-8320

CERTIFICATE OF ASSAY

TO Cyprus Anvil Mining Corporation

330 - 355 Burrard St.

Vancouver, B.C. V6C 2G8 Attention: Dr. G. Simpson

Certificate No. K-2716

Date May 8, 1980

I hereby certify that the following are the results of assays made by us upon the herein described drill core samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		Ounces Per Ton	g/tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent
1	1551		20	2.38	.23	.35				
2	1552		65	4.00	6.16	.17				

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.

cc Mr. Darryl Hanson

Registered Assayer, Province of British Columbia



Kamloops Research & Assay Laboratory Ltd.

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS, B.C. V1S 1A7
TELEPHONE 372-2784 TELEX 048-8320

CERTIFICATE OF ASSAY

TO Cyprus Anvil Mining Corporation

330 - 355 Burrard St.

Vancouver, B.C. V6C 2G8

Attention: Dr. G. Simpson
cc Darryl Hanson

Certificate No. K-2704

Date May 1, 1980

I hereby certify that the following are the results of assays made by us upon the herein described drill core samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		Ounces Per Ton	Ounces Per Ton	Percent	Percent	Percent	Percent	Percent	Percent	Percent
1	1520		12	.80	.89	.03				
2	1525		43	3.05	2.30	.15				
3	1526		23	1.16	.83	.18				
4	1527		46	2.84	4.50	.11				
5	1528		23	1.18	2.14	.38				
6	1529		25	.90	.44	.40				
7	1530		13	.29	.08	.45				
8	1531		12	.41	.46	.09				
9	1532		57	3.46	5.81	.06				
10	1533		25	1.92	1.30	.08				
11	1534		50	2.56	2.73	.20				
12	1535		11	.51	.46	.08				
13	1536		20	.87	1.07	.26				
14	1537		49	2.89	5.26	.06				
15	1538		42	2.51	3.68	.12				
16	1539		32	1.73	1.64	.17				
17	1540		78	4.28	8.13	.19				
18	1541		101	6.53	13.91	.08				
19	1542		77	4.26	8.17	.16				
20	1543		58	3.48	6.47	.08				

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.


Registered Assayer Province of British Columbia



Kamloops Research & Assay Laboratory Ltd.

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS 2

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS, B.C. V1S 1A7
TELEPHONE 372-2784 TELEX 048-8320

CERTIFICATE OF ASSAY

TO Cyprus Anvil Mining Corporation

Certificate No. K-2704

Date May 1, 1980

I hereby certify that the following are the results of assays made by us upon the herein described drill core samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		Ounces Per Ton	Ounces Per Ton	Percent	Percent	Percent	Percent	Percent	Percent	Percent
21	1544		27	1.20	1.48	.27				
22	1545		11	.30	.51	.33				
23	1546		43	2.92	2.82	.19				
24	1547		64	3.62	8.40	.09				
25	1548		105	5.84	11.09	.22				
26	1549		10	.21	.40	.37				
27	1550		21	.52	.80	.51				
	<u>Repeats</u>									
	1520		11	.63	.89	.03				
	1525		41	2.89	2.30	.15				
	<u>Standards</u>									
	100		95	5.41	8.86	.11				
	200		82	4.94	6.64	.16				
	300		40	2.28	4.38	.04				
	MP-1		58	1.87	-	2.09				
	RU-1		11	-	2.28	.85				
	KC-1		1140	7.04	-	.11				

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.

DAB for OESP
Registered Assayer, Province of British Columbia



Kamloops Research & Assay Laboratory Ltd.

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS, B.C. V1S 1A7
TELEPHONE 372-2784 TELEX 048-8320

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS

CERTIFICATE OF ASSAY

TO Cyprus Anvil Mining Corporation

330 - 355 Burrard St.

Vancouver, BC V6C 2G8 Attention: Dr. G. Simpson

Certificate No. K-2691

Date April 23, 1980

I hereby certify that the following are the results of assays made by us upon the herein described DY Core samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		Ounces Per Ton	g/tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent
1	1501		37	2.71	2.81	.11				
2	1502		5	.05	.77	.65				
3	1503		54	3.84	3.11	.24				
4	1504		24	2.02	1.93	.48				
5	1505		86	9.55	10.14	.26				
6	1506		104	8.82	10.24	.09				
7	1507		118	8.26	9.45	.08				
8	1508		42	2.50	5.66	.02				
9	1509		34	2.04	5.69	.02				
10	1510		23	1.44	2.76	.03				
11	1511		32	2.12	3.99	.03				
12	1512		27	2.04	2.98	.04				
13	1513		20	1.23	3.21	.03				
14	1514		32	2.00	4.80	.06				
15	1515		27	1.80	3.84	.06				
16	1516		23	1.49	3.22	.03				
17	1517		33	2.14	3.76	.03				
18	1518		13	.91	1.63	.05				
19	1519		10	.77	1.28	.02				
20	1521		9	.83	1.28	.04				

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.

Registered Assayer, Province of British Columbia



Kamloops Research & Assay Laboratory Ltd.

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS, B.C. V1S 1A7
TELEPHONE 372-2784 TELEX 048-8320

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS

CERTIFICATE OF ASSAY

TO Cyprus Anvil Mining Corporation

Certificate No. K-2691

Date April 23, 1980

I hereby certify that the following are the results of assays made by us upon the herein described DY Core samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		Ounces Per Ton	g/tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent
21	1522		10	.77	1.34	.06				
22	1523		23	1.76	3.21	.05				
23	1524		26	2.19	3.65	.03				
24	3530		98	7.10	7.78	.06				
25	3531		60	3.77	3.28	.21				
26	3532		78	5.98	5.10	.18				
27	3533		16	.43	.48	.26				
28	3534		9	.33	.49	.13				
29	3535		18	1.20	.72	.29				
30	3536		61	5.15	8.57	.14				
31	3537		45	3.54	1.53	.72				
32	3538		63	4.72	9.43	.05				
33	3539		48	2.02	2.54	.52				
34	3540		28	.44	.46	.50				
35	3541		49	2.36	2.98	.09				
36	3542		59	2.93	5.21	.11				
37	3543		41	2.52	1.94	.24				
38	3544		40	2.95	2.74	.25				
39	3545		29	.93	.35	.26				
40	3546		19	.45	.18	.09				

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.

Das for Das
Registered Assayer, Province of British Columbia



Kamloops Research & Assay Laboratory Ltd.

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS, B.C. V1S 1A7
TELEPHONE 372-2784 TELEX 048-8320

CERTIFICATE OF ASSAY

TO Cyprus Anvil Mining Corporation

Certificate No. K-2691

Date April 23, 1980

I hereby certify that the following are the results of assays made by us upon the herein described DY Core samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		Ounces Per Ton	g/tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent
41	3547		20	.29	.12	.15				
42	3548		16	.47	.17	.25				
43	3549		40	2.48	1.34	.24				
01 44	3550		29	1.54	.93	.30				
	<u>Repeats</u>									
	1513 -02		22	1.27	3.32	.03				
	3532 -01		78	5.98	5.12	.18				
	3545 -01		29	.92	.34	.26				
	<u>Standards</u>									
1st Run	100		95	5.40	8.92	.11				
	200		82	4.86	6.62	.16				
	300		40	2.31	4.43	.04				
	RU-1		7	-	2.28	.85				
2nd Run	MP-1		58	1.80	15.8	-				
	100		95	5.33	8.90	.11				
	200		82	4.95	6.77	.16				
	300		40	2.31	4.42	.04				
	RU-1		7	-	2.28	.85				
	MP-1		58	1.85	16.0	2.09				

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.

cc Darryl Hanson


Registered Assayer, Province of British Columbia



Kamloops Research & Assay Laboratory Ltd.

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS, B.C. V1S 1A7
TELEPHONE 372-2784 TELEX 048-8320

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS

Dy

CERTIFICATE OF ASSAY

TO Cyprus Anvil Mining Corporation

330 - 355 Burrard

Vancouver, B.C. V6C 2G8

ATTENTION: Dr. G. Simpson

Certificate No. K-2678

Date April 17, 1980

I hereby certify that the following are the results of assays made by us upon the herein described drill samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		Ounces Per Ton	g/tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent
1	X 3521		29	2.15	1.37	.19				
2	X 3522		48	3.20	2.36	.44				
3	X 3523		41	2.94	2.62	.26				
4	X 3524		32	2.31	1.83	.20				
5	X 3524		25	1.38	1.95	.10				
6	X 3526		56	4.04	3.94	.26				
7	X 3527		46	2.92	2.28	.35				
8	X 3528		6	.56	.88	.06				
9	X 3529		29	2.29	1.68	.26				

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.

cc Mr. Darryl Hanson

Registered Assayer, Province of British Columbia

79-X-01



Kamloops Research & Assay Laboratory Ltd.

2095 WEST TRANS CANADA HIGHWAY--KAMLOOPS, B.C. V1S 1A7
TELEPHONE 372-2784 - TELEX 048-8320

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS

CERTIFICATE OF ASSAY

TO Cyprus Anvil Mining Corporation,
330 - 355 Burrard Street,
Vancouver, B. C. V6C 2G8

Attention: Dr. G. Simpson

Certificate No. K-2000
Date May 2, 1979.

I hereby certify that the following are the results of assays made by us upon the herein described DY core samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		Ounces Per Ton	Grams/MT Ounces Per Ton	Percent	Percent	Percent	Percent	Percent	Percent	Percent
1	X-0007		5	.06	.02	.36				
2	0008		6.5	.22	.10	.26				
3	0009		7	.38	.14	.13				
4	0010		4	.09	.02	.10				
5	0011		5	.48	.15	.05				
6	0012		18	.79	.46	.35				
7	0013		11	.52	.23	.31				
8	0014		5	.14	.06	.24				
9	0015		3.5	.10	.04	.13				
10	0016		4	.12	.08	.02				
11	0017		6	.11	.04	.02				
12	0018		4	.09	.02	.01				
13	0019		Tr	.02	.02	.08				
14	0020		Tr	.01	.01	.04				
15	0021		6	.11	.05	.02				
16	0022		Tr	.02	.01	.01				
17	0023		8	.12	.06	.02				
18	0024		Tr	.04	.02	.01				
19	0025		3	.07	.04	.12				
20	X-0026		4	.08	.04	.29				

NOTE:

Rejects retained three weeks
Pulps retained three months
unless otherwise arranged.

.....*R. Blunder*.....
Registered Assayer, Province of British Columbia



Kamloops Research & Assay Laboratory Ltd.

2095 WEST TRANS CANADA HIGHWAY—KAMLOOPS, B.C. V1S 1A7
TELEPHONE 372-2784 - TELEEX 048-8320

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS

CERTIFICATE OF ASSAY

TO Cyprus Anvil Mining Corporation

Certificate No. K-2000

Date May 2, 1979.

I hereby certify that the following are the results of assays made by us upon the herein described DY core samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		Ounces Per Ton	Grams/MT X Ounces Per Ton	Percent	Percent	Percent	Percent	Percent	Percent	Percent
21	X-0027		2.5	.13	.06	.15				
22	0028		27	2.07	1.88	.39				
23	0029		39	2.20	3.19	.08				
24	0030		23	1.30	3.32	.06				
25	0031		30	2.02	3.81	.07				
26	0032		32	2.16	5.27	.11				
27	0033		49	2.45	4.95	.05				
28	0034		34	1.93	4.45	.02				
29	0035		27.5	1.65	3.65	.02				
30	0036		26	1.61	3.13	.03				
31	0037		25	1.40	2.07	.03				
32	0038		21	.98	2.22	.04				
33	0039		27	2.01	3.65	.03				
34	X-0040		40	2.05	3.71	.06				

Tr denotes "trace"

c.c. Mr. S. Buziak

NOTE:

Rejects retained three weeks
Pulps retained three months
unless otherwise arranged.

R. S. Lee

Registered Assayer, Province of British Columbia

CYPRUS ANVIL MINING CORPORATION

DY 79-X-01

GEOCHEMICAL LOG

Kamloops Research & Assay Lab.

<u>From</u>	<u>To</u>	<u>Int.</u>	<u>Sample No.</u>	<u>Ag GMS/MT</u>	<u>Pb %</u>	<u>Zn %</u>	<u>Pb+Zn %</u>	<u>S.G.</u>	<u>Cu %</u>	<u>BaO %</u>	<u>Au GMS/MT</u>	<u>Po %</u>	<u>Py %</u>	<u>Hg %</u>
509.8	511.4	1.6	0007	5.0	0.06	0.02			0.36					
511.4	512.9	1.5	0008	6.5	0.22	0.10			0.26					
512.9	514.9	2.0	0009	7.0	0.38	0.14			0.13					
514.9	517.0	2.1	0010	4.0	0.09	0.02			0.10					
517.0	518.7	1.7	0011	5.0	0.48	0.15			0.02					
518.7	520.7	2.0	0012	18.0	0.79	0.46			0.35					
520.7	522.7	2.0	0013	11.0	0.52	0.23			0.31					
522.7	524.3	1.6	0014	5.0	0.14	0.06			0.24					
524.3	525.7	1.4	0015	3.5	0.10	0.04			0.13					
525.7	526.7	1.0	0016	4.0	0.12	0.08			0.02					
526.7	528.1	1.4	0017	6.0	0.11	0.04			0.02					
528.1	528.8	0.7	0018	4.0	0.09	0.02			0.01					
528.8	530.4	1.6	0019	TR	0.02	0.02			0.08					
532.3	532.9	0.6	0020	TR	0.01	0.01			0.04					
532.9	535.0	2.1	0021	6.0	0.11	0.05			0.02					
535.0	536.0	1.0	0022	TR	0.02	0.01			0.01					
536.0	536.7	0.7	0023	8.0	0.12	0.06			0.02					
536.7	538.0	1.3	0024	TR	0.04	0.02			0.01					
538.0	540.3	2.3	0025	3.0	0.07	0.04			0.12					
545.4	546.0	0.6	0026	4.0	0.08	0.04			0.29					
547.3	549.2	1.9	0027	2.5	0.13	0.06			0.15					
549.2	550.1	0.9	0028	27.0	2.07	1.88	3.95		0.39					
554.5	556.5	2.0	0029	39.0	2.20	3.19	5.39		0.08					
556.5	558.5	2.0	0030	23.0	1.30	3.32	4.62		0.06					
558.5	560.5	2.0	0031	30.0	2.02	3.81	5.83		0.07					
560.5	561.6	1.1	0032	32.0	2.16	5.27	7.53		0.11					

DY 79-X-01

GEOCHEMICAL LOG

Page 2 of 2

<u>From</u>	<u>To</u>	<u>Int.</u>	<u>Sample No.</u>	<u>Ag/AA GMS/MT</u>	<u>Ag/FA GMS/MT</u>	<u>Pb %</u>	<u>Zn %</u>	<u>Pb+Zn %</u>	<u>S.G.</u>	<u>Cu %</u>	<u>BaO %</u>	<u>Au GMS/MT</u>	<u>Po %</u>	<u>Py %</u>	<u>Hg %</u>
650.9	652.9	2.0	0033	49.0		2.45	4.95	7.40		0.05					
652.9	654.9	2.0	0034	34.0		1.93	4.45	6.38		0.02					
654.9	656.9	2.0	0035	27.5		1.65	3.65	5.30		0.02					
656.9	658.9	2.0	0036	26.0		1.61	3.13	4.74		0.03					
658.9	660.9	2.0	0037	25.0		1.40	2.07	3.47		0.03					
660.9	662.7	1.8	0038	21.0		0.98	2.22	3.20		0.04					
681.3	682.6	1.3	0039	27.0		2.01	3.65	5.66		0.03					
682.6	683.5	1.5	0040	40.0		2.05	3.71	5.76		0.06					

BEST SECTIONS:

558.5	561.6	3.1		30.6		2.06	4.33	6.39							
650.9	654.9	4.0		41.5		2.19	4.70	6.89							

ANVIL VCR

KRAL KAM

ATTN GLEN SIMPSON

ASSAY RESULTS

Horizon	Lithofaces	From - To	Interval	AG	PB	ZN	CU		
4	4K/EC	X-007	509.8 - 511.4	1.6 m	5	.06	.02	.36	
		8	511.4 - 512.9	1.5	6.5	.22	.10	.26	
		9	512.9 - 514.9	2.0	7	.38	.14	.13	
		10	514.9 - 517.0	2.1	4	.09	.02	.10	
		11	517.0 - 518.7	1.7	5	.48	.15	.02	
		12	518.7 - 520.7	2.0	18	.79	.46	.35	
		13	520.7 - 522.7	2.0	11	.52	.23	.31	
		14	522.7 - 524.3	1.6	5	.14	.06	.24	
		15	524.3 - 525.7	1.4	3.5	.10	.04	.13	
		16	525.7 - 526.7	1.0	4	.12	.08	.02	
		17	526.7 - 528.1	1.4	6	.11	.04	.02	
		18	528.1 - 528.8	0.7	4	.09	.02	.01	
		19	528.8 - 530.4	1.6	TR	.02	.02	.08	
		20	532.3 - 532.9	0.6	TR	.01	.01	.04	
		21	532.9 - 535.0	2.1	6	.11	.05	.02	
		22	535.0 - 536.6	1.6	TR	.02	.01	.01	
		23	536.6 - 536.7	0.1	8	.12	.06	.02	
		24	536.7 - 538.0	1.3	TR	.04	.02	.01	
		25	538.0 - 640.3	2.3	3	.07	.04	.12	
		26	545.4 - 546.0	0.6	4	.08	.04	.29	
		27	547.3 - 549.2	1.9	2.5	.13	.06	.15	
		28	549.2 - 550.1	0.9	27	2.07	1.88	3.95	.39
		29	554.5 - 556.5	2.0	39	2.20	3.19	5.39	.08
		30	556.5 - 558.5	2.0	23	1.30	3.32	4.62	.06
		31	558.5 - 560.5	2.0	30	2.02	3.81	5.83	.07
32	560.5 - 561.6	1.1	32	2.16	5.27	7.53	.11		
2/3	1/A	33	650.9 - 652.9	2.0	49	2.45	4.95	7.40	.05
		34	652.9 - 654.9	2.0	34	1.93	4.45	6.38	.02
		35	654.9 - 656.9	2.0	27.5	1.65	3.65	5.30	.02
		36	656.9 - 658.9	2.0	26	1.61	3.13	4.74	.03
		37	658.9 - 660.9	2.0	25	1.40	2.07	3.47	.03
		38	660.9 - 662.7	1.8	21	.98	2.22	3.20	.04
		39	662.7 - 667.4	4.7	27	2.01	3.65	5.66	.03
		40	667.4 - 683.5	16.1	40	2.05	3.71	5.76	.06

2 - Sections

Horizon 1/1 : 554.5 - 561.6 7.1M at 5.63% Pb+Zn

Horizon 2/3 : 650.9 - 656.9 6.0M at 6.36% Pb+Zn

REGARDS DEREK

KRAL KAM

79-X-02



Kamloops Research & Assay Laboratory Ltd.

2095 WEST TRANS CANADA HIGHWAY-KAMLOOPS, B.C. V1S 1A7
TELEPHONE 372-2784 - TELEX 048-8320

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS

CERTIFICATE OF ASSAY

TO Cyprus Anvil Mining Corporation,
330 - 355 Burrard Street,
Vancouver, B. C. V6C 2G8

Attention: Dr. G. Simpson

Certificate No. K-2017
Date May 24, 1979.

I hereby certify that the following are the results of assays made by us upon the herein described DY core samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		Ounces Per Ton	Gm/Metric Ton Ounces Per Ton	Percent	Percent	Percent	Percent	Percent	Percent	Percent
1	0041		2	.01	.01	.03				
2	0042		2	Tr	.01	.04				
3	0043		1	Tr	.01	.04				
4	0044		1	Tr	.01	.01				
5	0045		1	Tr	.02	.01				
6	0046		2	.08	.03	.01				
7	0047		3	.13	.36	.02				
8	0048		1	Tr	.04	.02				
9	0049		.5	Tr	.03	.01				
10	0050		.5	Tr	.02	.01				
11	0051		.5	Tr	.015	.01				
12	0052		1	Tr	.02	.01				
13	0053		1	.04	.08	.02				
14	0054		2	.11	.12	.02				
15	0055		16	.03	.03	.02				
16	0056		1	Tr	.03	.01				
17	0057		2	.06	.08	.03				
18	0058		2	.05	.06	.02				
19	0059		11	.89	1.65	.02				
20	0060		11	.87	1.63	.02				

56²

DY 02

NOTE:

Rejects retained three weeks
Pulps retained three months
unless otherwise arranged.

R. A. Blundell
Registered Assayer, Province of British Columbia



Kamloops Research & Assay Laboratory Ltd.

2095 WEST TRANS CANADA HIGHWAY—KAMLOOPS, B.C. V1S 1A7
TELEPHONE 372-2784 · TELEX 048-8320

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS

CERTIFICATE OF ASSAY

TO Cyprus Anvil Mining Corporation

Certificate No. K-2017

Date May 24, 1979.

I hereby certify that the following are the results of assays made by us upon the herein described DY core samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		Ounces Per Ton	Gm/Metric Ton Ounces Per Ton	Percent	Percent	Percent	Percent	Percent	Percent	Percent
21	0061		28	1.98	2.41	.02				
22	0062		3	.14	.22	.01				
23	0063		16	.73	2.24	.02				
24	0064		3	.13	.40	.01				
25	0065		4	.12	.20	.01				
26	0066		4	.12	.35	.01				
27	0067		8	.07	.10	.01				
28	0068		3	.12	.40	.01				
29	0069		34	1.96	2.58	.01				
30	0070		2	.04	.07	.01				
31	0071		3	.02	.08	.01				
32	0072		100	6.27	10.8	.03				
33	0073		85	7.50	11.1	.03				
34	0074		57	3.80	6.33	.07				
35	0075		5	.55	.78	.02				
36	0076		2	.04	.07	.01				

Tr denotes "trace"

c.c. Mr. S. Buziak

NOTE:

Rejects retained three weeks
Pulps retained three months
unless otherwise arranged.

R. P. Blundell
.....
Registered Assayer, Province of British Columbia

CYPRUS ANVIL MINING CORPORATION

DY 79-X-02

GEOCHEMICAL LOG

Kamloops Research & Assay Lab.

<u>From</u>	<u>To</u>	<u>Int.</u>	<u>Sample No.</u>	<u>Ag/AA GMS/MT</u>	<u>Ag/FA GMS/MT</u>	<u>Pb %</u>	<u>Zn %</u>	<u>Pb+Zn %</u>	<u>S.G.</u>	<u>Cu %</u>	<u>BaO %</u>	<u>Au GMS/MT</u>	<u>Po%</u>	<u>Py %</u>	<u>Hg %</u>
577.6	579.6	2.0	0059	11.0		0.39	1.65	2.54		0.02					
579.6	581.6	2.0	0060	11.0		0.87	1.63	2.50		0.02					
581.6	583.5	1.9	0061	28.0		1.98	2.41	4.39		0.02					
583.5	585.6	2.1	0062	3.0		0.14	0.22			0.01					
585.6	587.8	2.2	0063	16.0		0.73	2.24	2.97		0.02					
587.8	589.2	1.4	0064	3.0		0.14	0.40			0.01					
589.2	590.0	0.8	0065	4.0		0.12	0.20			0.01					
590.0	592.1	2.1	0066	4.0		0.12	0.35			0.01					
592.1	593.2	1.1	0067	8.0		0.07	0.10			0.01					
593.2	594.0	0.8	0068	3.0		0.12	0.40			0.01					
595.4	596.9	1.5	0069	34.0		1.96	2.58	4.54		0.01					
596.9	598.4	1.5	0070	2.0		0.04	0.73			0.01					
598.4	600.0	1.6	0071	3.0		0.02	0.08			0.01					
600.0	601.5	1.5	0072	100.0		6.27	10.85	17.12		0.03					
601.5	602.5	1.0	0073	85.0		7.50	11.10	18.60		0.03					
606.6	607.6	1.0	0074	57.0		3.80	6.33	10.13		0.07					
607.6	608.3	0.7	0075	5.0		0.55	0.78			0.02					
646.7	648.5	1.8	0076	2.0		0.04	0.07			0.01					

BEST SECTION:

600.0	602.5	2.5		94.0		6.76	10.94	17.70							
-------	-------	-----	--	------	--	------	-------	-------	--	--	--	--	--	--	--

79-X-03



Kamloops Research & Assay Laboratory Ltd.

2095 WEST TRANS CANADA HIGHWAY-KAMLOOPS, B.C. V1S 1A7
TELEPHONE 372-2784 TELEX 048-8320

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS 2.

CERTIFICATE OF ASSAY

04

TO Cyprus Anvil Mining Corporation

Certificate No. K-2090

Date June 22, 1979.

I hereby certify that the following are the results of assays made by us upon the herein described DY drill core samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		Ounces Per Ton	Grams/M Ton XXXXXXXX XXXXXXXX	Percent	Percent	Percent	Percent	Percent	Percent	Percent
16	X 0262		2	.05	.03	.02				
17	0263		2	.05	.04	.01				
18	0264		3	.05	.03	.06				
19	0265		6	.03	.01	.11				
20	0266		8	.04	.01	.28				
21	0267		3	.02	.01	.07				
22	0268		7	.01	.02	.19				
23	X 0287		50	2.21	5.19	.02				
24	0288		12	.68	1.03	.03				
25	0289		46	3.62	3.41	.02				
25	X 0290		40	2.64	3.34	.01				
	(03) X 0250 Repeat		25	1.88	.94	.03				
	X 0260 Repeat		15	.62	.34	.28				
	Std. 200		80	4.84	6.67	.16				
	300		41	2.27	4.32	.04				
	RU-1		-	-	2.14	.85				
	100		-	5.44	-	.11				
	MP-1		57	1.88	-	-				

NOTE:

Rejects retained three weeks
Pulps retained three months
unless otherwise arranged.

.....D.A.B. for P&S.....
Registered Assayer, Province of British Columbia



Kamloops Research & Assay Laboratory Ltd.

2095 WEST TRANS CANADA HIGHWAY-KAMLOOPS, B.C. V1S 1A7
TELEPHONE 372-2784 - TELEX 048-8320

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS

CERTIFICATE OF ASSAY

03

TO Cyprus Anvil Mining Corporation,

330 -355 Burrard Street,

Vancouver, B. C. V6C 2G8 Attention: Dr. G. Simpson

Certificate No. K-2090

Date June 22, 1979.

I hereby certify that the following are the results of assays made by us upon the herein described DY drill core samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		Ounces Per Ton	Grams/M Ton XXXXXX XXXXXX	Percent	Percent	Percent	Percent	Percent	Percent	Percent
1	X 0112		25	1.31	2.70	.16				
2	0248		5	.27	.31	.03				
3	0249		2	.09	.13	.01				
4	0250		25	1.85	.95	.03				
5	0251		30	.02	.88	.06				
6	0252		16	.01	.26	.06				
7	0253		17	1.07	.30	.10				
8	0254		7	.08	.16	.12				
9	0255		12	.37	.11	.13				
10	0256		4	.24	.08	.03				
11	0257		10	.06	.08	.02				
12	0258		32	2.03	2.41	.09				
13	0259		15	.69	1.04	.17				
14	0260		16	.62	.35	.29				
15	X 0261		20	.78	.80	.32				

NOTE:
Rejects retained three weeks
Pulps retained three months
unless otherwise arranged.

.....
Registered Assayer, Province of British Columbia



Kamloops Research & Assay Laboratory Ltd.

2095 WEST TRANS CANADA HIGHWAY-KAMLOOPS, B.C. V1S 1A7
TELEPHONE 372-2784 TELEX 048-8320

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS

CERTIFICATE OF ASSAY

TO Cyprus Anvil Mining Corporation,
330 - 355 Burrard Street,
Vancouver, B. C. V6C 2G8

Attention: Dr. G. Simpson.

Certificate No. K-2039

Date June 4, 1979.

I hereby certify that the following are the results of assays made by us upon the herein described DY core samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		Ounces Per Ton	Grams/MT Ounces Per Ton	Percent	Percent	Percent	Percent	Percent	Percent	Percent
1	0077		6.5	.42	.14	.07				
2	0078		2	.11	.02	.03				
3	0079		8	.66	.22	.04				
4	0080		4	.34	.14	.04				
5	0081		3	.26	.03	.03				
6	0082		3	.23	.04	.02				
7	0083		2	.04	.02	.03				
8	0084		2	.10	.04	.07				
9	0085		1	.13	.11	.02				
10	0086		16	.91	.70	.25				
11	0087		2	.13	.07	.04				
12	0088		30	1.79	.91	.23				
13	0089		45	3.34	1.92	.17				
14	0090		28	.75	.31	.22				
15	0091		27	.38	.13	.33				
16	0092		7	.12	.05	.37				
17	0093		13	.11	.04	.57				
18	0094		11	.11	.07	.45				
19	0095		16	.65	.58	.44				
20	0096		9	.15	.14	.40				

NOTE:

Rejects retained three weeks
Pulps retained three months
unless otherwise arranged.

Registered Assayer, Province of British Columbia



Kamloops Research & Assay Laboratory Ltd.

2095 WEST TRANS CANADA HIGHWAY-KAMLOOPS, B.C. V1S 1A7
TELEPHONE 372-2784 - TELEX 048-8320

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS

CERTIFICATE OF ASSAY

TO Cyprus Anvil Mining Corporation

K-2039

Certificate No. _____

Date June 4, 1979.

I hereby certify that the following are the results of assays made by us upon the herein described DY Core samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		Ounces Per Ton	Grams/MT OUNCES PER TON	Percent	Percent	Percent	Percent	Percent	Percent	Percent
21	0097		5	.04	.03	.32				
22	0098		6	.06	.05	.31				
23	0099		.5	.02	.02	.01				
24	0100		2	.04	.02	.29				
25	0101		Tr	.01	.03	.02				
26	0102		2	.03	.03	.02				
27	0103		1	.02	.03	.02				
28	0104		1	.02	.02	.02				
29	0105		8	.10	.05	.11				
30	0106		2	.03	.03	.06				
31	0107		2	.03	.02	.05				
32	0108		2	.02	.05	.08				
33	0109		7	.13	.05	.12				
34	0110		36	1.94	3.28	.02				
35	0111		29	1.48	2.72	.03				
36	0112	-- No Sample	-	-	-	-				
37	0113		17	1.02	.73	.10				
38	0114		10	.44	.18	.01				
39	0115		62	3.51	5.52	.11				
40	0116		45	4.11	5.77	.05				

NOTE:

Rejects retained three weeks
Pulps retained three months
unless otherwise arranged.

Tr denotes "trace"

Registered Assayer, Province of British Columbia



Kamloops Research & Assay Laboratory Ltd.

2095 WEST TRANS CANADA HIGHWAY—KAMLOOPS, B.C. V1S 1A7
 TELEPHONE 372-2784 - TELEX 048-8320

B.C. LICENSED ASSAYERS
 GEOCHEMICAL ANALYSTS

CERTIFICATE OF ASSAY

TO Cyprus Anvil Mining Corporation

Certificate No. K-2039

Date June 4, 1979.

I hereby certify that the following are the results of assays made by us upon the herein described DY Core samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		Ounces Per Ton	Grams/MT Ounces Per Ton	Percent	Percent	Percent	Percent	Percent	Percent	Percent
41	0117		6	.15	.07	.05				
42	0118		43	1.51	2.42	.12				
43	0119		8	.17	.05	.07				
44	0120		14	.30	.14	.16				
45	0121		146	6.56	4.29	.16				
46	0122		27	.66	.35	.16				
#3 47	0123		6	.36	.34	.07				
48	0124		14	.54	.58	.05				
49	0125		10	.39	.50	.06				
50	0126		27	1.02	.51	.08				
51	0127		93	4.79	11.95	.06				
52	0128		50	2.72	5.93	.03				
53	0129		69	3.60	7.13	.05				
54	0130		58	3.66	6.87	.06				
#4 55	0131		21	1.18	2.11	.07				
56	0132		25	1.70	2.03	.05				

NOTE:

Rejects retained three weeks
 Pulps retained three months
 unless otherwise arranged.

c.c. Mr. S. Buziak.

R. B. Blew dell
 Registered Assayer, Province of British Columbia

GEOCHEMICAL LOG

Kamloops Research & Assay Lab.

<u>From</u>	<u>To</u>	<u>Int.</u>	<u>Samp.</u> <u>No.</u>	<u>Ag/AA</u> <u>GMS/MT</u>	<u>Ag/FA</u> <u>GMS/MT</u>	<u>Pb %</u>	<u>Zn %</u>	<u>Pb+Zn</u> <u>%</u>	<u>S.G.</u>	<u>Cu %</u>	<u>BaO %</u>	<u>Au</u> <u>GMS/MT</u>	<u>Po %</u>	<u>Py %</u>	<u>Hg %</u>	<u>Unit</u>
578.3	580.4	2.1	0077	6.5		0.42	0.14			0.07						4L7/4
580.4	581.5	1.1	0078	2.0		0.11	0.02			0.03						4A3
581.5	583.5	2.0	0079	8.0		0.66	0.22			0.04						4C/4L
583.5	585.5	2.0	0080	4.0		0.34	0.14			0.04						4L0
587.5	588.5	1.0	0081	3.0		0.26	0.03			0.03						4L0
588.5	590.1	1.6	0082	3.0		0.23	0.04			0.02						509
590.1	592.1	2.0	0083	2.0		0.04	0.02			0.03						4L7/4
592.1	594.1	2.0	0084	2.0		0.10	0.04			0.07						4L7/4
594.1	595.9	1.8	0085	1.0		0.13	0.11			0.02						4L7/4
595.9	597.1	1.2	0086	16.0		0.91	0.70			0.25						4G4
597.1	598.1	1.0	0087	2.0		0.13	0.07			0.04						4L0
598.1	599.3	1.2	0088	30.0		1.79	0.91			0.23						4G4
599.3	600.6	1.3	0089	45.0		3.34	1.92	5.26		0.17						4G4
600.6	602.3	1.7	0090	28.0		0.75	0.31			0.22						4K6/4
602.3	604.5	2.2	0091	27.0		0.38	0.13			0.33						4E0
604.5	606.7	2.2	0092	7.0		0.12	0.05			0.37						4E0
606.7	608.7	2.0	0093	13.0		0.11	0.04			0.57						4L/4C
608.7	610.2	1.5	0094	11.0		0.11	0.07			0.45						4D0
610.2	612.0	1.8	0095	16.0		0.65	0.58			0.44						4D4
612.0	614.0	2.0	0096	9.0		0.15	0.14			0.40						4D0
614.0	615.1	1.1	0097	5.0		0.04	0.03			0.32						4D0
615.1	616.6	1.5	0098	6.0		0.06	0.05			0.31						4A0
621.2	623.2	2.0	0099	0.5		0.02	0.02			0.01						5A9
623.2	624.0	0.8	0100	2.0		0.04	0.02			0.29						4C0
624.4	626.4	2.0	0101	Tr.		0.01	0.03			0.02						4L0
626.4	628.4	2.0	0102	2.0		0.03	0.03			0.02						4L0
628.4	630.1	1.7	0103	1.0		0.02	0.03			0.02						4L0
630.1	631.9	1.8	0104	1.0		0.02	0.02			0.02						5A9

DY 79-X-03

GEOCHEMICAL LOG

<u>From</u>	<u>To</u>	<u>Int.</u>	<u>Samp. No.</u>	<u>Ag/AA GMS/MT</u>	<u>Ag/FA GMS/MT</u>	<u>Pb %</u>	<u>Zn %</u>	<u>Pb+Zn %</u>	<u>S.G.</u>	<u>Cu %</u>	<u>BaO %</u>	<u>Au GMS/MT</u>	<u>Po %</u>	<u>Py %</u>	<u>Hg %</u>	<u>Unit</u>
639.0	639.8	0.8	0105	8.0		0.10	0.05			0.11						4C0
639.8	641.8	2.0	0106	2.0		0.03	0.03			0.06						4L0
641.8	643.8	2.0	0107	2.0		0.03	0.02			0.05						4L0
643.8	644.4	0.6	0108	2.0		0.02	0.05			0.08						4L0
644.4	646.3	1.9	0109	7.0		0.13	0.05			0.12						4C0
700.8	702.8	2.0	0110	36.0		1.94	3.28	5.22		0.02						4A4
702.8	704.8	2.0	0111	29.0		1.48	2.72	4.20		0.03						4A4
704.8	706.4	1.6	0112	25.0		1.31	2.70	4.01		0.16						4A4
713.6	715.7	2.1	0248	5.0		0.27	0.31			0.03						4A0
717.2	719.3	2.1	0249	2.0		0.09	0.13			0.01						4A0
731.3	733.4	2.1	0250	25.0		1.88	0.94			0.03						4L4
733.4	735.4	2.0	0251	30.0		0.02	0.88			0.06						4A0
735.4	737.4	2.0	0252	16.0		0.01	0.26			0.06						4A0
737.4	739.4	2.0	0253	17.0		1.07	0.30			0.10						4A0
739.4	740.7	1.3	0254	7.0		0.08	0.16			0.12						4A0
740.7	741.7	1.0	0255	12.0		0.37	0.11			0.13						4A0
759.7	761.2	1.5	0256	4.0		0.24	0.08			0.03						4A0
761.2	762.8	1.6	0257	10.0		0.06	0.08			0.02						4A0
821.9	823.2	1.3	0258	32.0		2.03	2.41	4.44		0.09						4A0
823.2	824.7	1.5	0259	15.0		0.69	1.04			0.17						4A0
824.7	826.0	1.3	0260	15.0		0.62	0.34			0.28						4E0
826.0	827.8	1.8	0261	20.0		0.78	0.80			0.32						-

79-X-04



Kamloops Research & Assay Laboratory Ltd.

2095 WEST TRANS CANADA HIGHWAY—KAMLOOPS, B.C. V1S 1A7
TELEPHONE 372-2784 - TELEX 048-8320

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS 2.

CERTIFICATE OF ASSAY

04

TO Cyprus Anvil Mining Corporation

Certificate No. K-2090

Date June 22, 1979.

I hereby certify that the following are the results of assays made by us upon the herein described DY drill core samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		Ounces Per Ton	Grams/M Ton XXXXXX XXXXXX	Percent	Percent	Percent	Percent	Percent	Percent	Percent
16	X 0262		2	.05	.03	.02				
17	0263		2	.05	.04	.01				
18	0264		3	.05	.03	.06				
19	0265		6	.03	.01	.11				
20	0266		8	.04	.01	.28				
21	0267		3	.02	.01	.07				
22	0268		7	.01	.02	.19				
23	X 0287		50	2.21	5.19	.02				
24	0288		12	.68	1.03	.03				
25	0289		46	3.62	3.41	.02				
25	X 0290		40	2.64	3.34	.01				
	X 0250 Repeat		25	1.88	.94	.03				
03	X 0260 Repeat		15	.62	.34	.28				
	Std. 200		80	4.84	6.67	.16				
	300		41	2.27	4.32	.04				
	RU-1		-	-	2.14	.85				
	100		-	5.44	-	.11				
	MP-1		57	1.88	-	-				

NOTE:

Rejects retained three weeks
Pulps retained three months
unless otherwise arranged.

.....
DAB for P&S
Registered Assayer, Province of British Columbia



Kamloops Research & Assay Laboratory Ltd.

2095 WEST TRANS CANADA HIGHWAY-KAMLOOPS, B.C. V1S 1A7
 TELEPHONE 372-2784 - TELEEX 048-8320

B.C. LICENSED ASSAYERS
 GEOCHEMICAL ANALYSTS

CERTIFICATE OF ASSAY

TO Cyprus Anvil Mining Corporation

Certificate No. K-2039

Date June 4, 1979.

I hereby certify that the following are the results of assays made by us upon the herein described DY Core samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		Ounces Per Ton	Grams/MT XXXXXXXX	Percent	Percent	Percent	Percent	Percent	Percent	Percent
41	0117		6	.15	.07	.05				
42	0118		43	1.51	2.42	.12				
43	0119		8	.17	.05	.07				
44	0120		14	.30	.14	.16				
45	0121		146	6.56	4.29	.16				
46	0122		27	.66	.35	.16				
47	0123		6	.36	.34	.07				
48	0124		14	.54	.58	.05				
49	0125		10	.39	.50	.06				
50	0126		27	1.02	.51	.08				
51	0127		93	4.79	11.95	.06				
52	0128		50	2.72	5.93	.03				
53	0129		69	3.60	7.13	.05				
54	0130		58	3.66	6.87	.06				
55	0131		21	1.18	2.11	.07				
56	0132		25	1.70	2.03	.05				

NOTE:

Rejects retained three weeks
 Pulps retained three months
 unless otherwise arranged.

c.c. Mr. S. Buziak.

.....
 Registered Assayer, Province of British Columbia

79-X-05



Kamloops Research & Assay Laboratory Ltd.

2095 WEST TRANS CANADA HIGHWAY—KAMLOOPS, B.C. V1S 1A7
 TELEPHONE 372-2784 · TELEX 048-8320

B.C. LICENSED ASSAYERS
 GEOCHEMICAL ANALYSTS

CERTIFICATE OF ASSAY

TO Cyprus Anvil Mining Corporation

Certificate No. K-2111

Date July 6, 1979.

I hereby certify that the following are the results of assays made by us upon the herein described DY drill core samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		Ounces Per Ton	gm/tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent
DY 05	79	X 0311	6	.51	.91	.03				
	80	0312	8	.58	1.08	.03				
	81	0313	17	1.74	3.04	Tr				
	82	0314	24	2.14	3.16	.04				
	83	0315	15	1.52	2.20	.05				
	84	0316	2	.15	.32	Tr				
	85	0317	15	.47	.87	.04				
	86	0318	62	4.08	2.92	.28				
DY 06	87	0319	101	6.52	8.83	.05				
	88	0320	81	7.32	5.50	.08				
	89	0321	35	2.77	1.54	.03				
	90	0322	63	4.62	3.73	.13				
	91	0323	62	4.63	3.52	.23				
	92	0324	28	2.01	2.17	.02				
	93	0325	46	2.77	1.69	.09				
	94	0326	91	7.47	6.96	.02				
	95	0327	171	15.96	8.79	.04				
	96	0328	170	15.29	9.31	.10				
	97	0329	248	23.76	6.85	.12				
	98	X 0330	245	21.13	4.59	.07				

NOTE:
 Rejects retained three weeks
 Pulp retained three months
 unless otherwise arranged.



 Registered Assayer, Province of British Columbia



Kamloops Research & Assay Laboratory Ltd.

2095 WEST TRANS CANADA HIGHWAY—KAMLOOPS, B.C. V1S 1A7
 TELEPHONE 372-2784 TELEX 048-8320

B.C. LICENSED ASSAYERS
 GEOCHEMICAL ANALYSTS

CERTIFICATE OF ASSAY

TO Cyprus Anvil Mining Corporation


Certificate No. K-2111

Date July 6, 1979.

I hereby certify that the following are the results of assays made by us upon the herein described DY drill core samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		Ounces Per Ton	gm/tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent
<i>ob</i> 139	X 0400		2	.03	.03	.10				
<i>V-119-R</i> 140	0439		1	.07	.37	.07				
141	0451		29	1.97	3.57	.13				
142	0452		56	3.17	5.01	.19				
<i>ob</i> 143	0453		15	.66	.47	.19				
144	0459		3	.20	.36	.01				
145	0460		22	1.31	3.50	.02				
146	0461		23	1.38	2.81	.02				
147	0462		35	1.69	3.85	.10				
148	0463		28	1.55	3.40	.01				
<i>ob</i> 149	0464		69	4.55	1.66	.05				
150	0465		5	.44	1.31	.01				
151	0466		5	.35	.49	.01				
152	0467		17	1.26	2.20	.02				
153	0468		9	.80	1.30	.01				
154	0469		7	.43	.97	.01				
155	0470		9	.57	.82	.01				
156	0471		8	.69	1.17	.01				
157	0472		7	.50	.25	.03				
158	X 0473		Tr	.07	.13	.03				

NOTE:
 Rejects retained three weeks
 Pulps retained three months
 unless otherwise arranged.



 Registered Assayer, Province of British Columbia



Kamloops Research & Assay Laboratory Ltd.

2095 WEST TRANS CANADA HIGHWAY—KAMLOOPS, B.C. V1S 1A7
 TELEPHONE 372-2784 - TELEX 048-8320

B.C. LICENSED ASSAYERS
 GEOCHEMICAL ANALYSTS

CERTIFICATE OF ASSAY

TO Cyprus Anvil Mining Corporation

Certificate No. K-2111

Date July 6, 1979.

I hereby certify that the following are the results of assays made by us upon the herein described DY drill core samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		Ounces Per Ton	gm/tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent
159	X 0474		6	.48	.87	.13				
160	0475		7	.32	.75	.19				
161	0476		15	.59	1.31	.27				
162	0477		9	.43	.61	.06				
163	0478		19	1.20	1.33	.08				
164	0479		34	2.15	3.19	.02				
165	0480		51	3.57	2.17	.02				
166	0481		33	2.71	1.41	.03				
167	0482		18	1.17	1.94	.03				
168	0483		80	5.01	7.15	.06				
169	X 0484		78	4.54	8.91	.08				

05

NOTE:
 Rejects retained three weeks
 Pulps retained three months
 unless otherwise arranged.

c.c. Mr. S. Buziak

DAB for Pess
 Registered Assayer, Province of British Columbia



Kamloops Research & Assay Laboratory Ltd.

2095 WEST TRANS CANADA HIGHWAY—KAMLOOPS, B.C. V1S 1A7
TELEPHONE 372-2784 - TELEX 048-8320

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS

2 (F)

CERTIFICATE OF ASSAY

TO Cyprus Anvil Mining Corporation

Certificate No. K-2100

Date June 29, 1979.

I hereby certify that the following are the results of assays made by us upon the herein described DY core samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		Ounces Per Ton	gm/tonne XXXXXXXXXX	Percent	Percent	Percent	Percent	Percent	Percent	Percent
15	X 0305		8	.11	.05	.02				
16	0306		8	.08	.05	.04				
17	0307		9	.23	.21	.19				
18	0308		42	2.97	2.21	.14				
19	0309		61	4.24	3.44	.17				
20	X 0310		88	4.71	4.39	.24				
	X 0307 Repeat		10	.22	.22	.20				
	* Standards:									
	MP-1		59	1.90	-	-				
	100		83	5.44	8.92	.11				
	200		82	4.99	6.68	.16				
	300		41	2.29	4.38	.04				
	RU-1		-	-	2.24	.85				
	* Standards same for both Vangorda and DY core									

M-X-05

77

NOTE:

Rejects retained three weeks
Pulps retained three months
unless otherwise arranged.

c.c. Mr. S. Buziak

R. A. Blundell
.....
Registered Assayer, Province of British Columbia



Kamloops Research & Assay Laboratory Ltd.

2095 WEST TRANS CANADA HIGHWAY—KAMLOOPS, B.C. V1S 1A7
TELEPHONE 372-2784 · TELEX 048-8320

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS

CERTIFICATE OF ASSAY

TO Cyprus Anvil Mining Corporation

Certificate No. K-2111

Date July 6, 1979

I hereby certify that the following are the results of assays made by us upon the herein described Vangorda & DY drill core samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		Ounces Per Ton	Ounces Per Ton	Percent	Percent	Percent	Percent	Percent	Percent	Percent
	Repeats and Standards									
	R V 0410 - V119		Tr	.15	.42	Tr				
	R V 0433 ✓		44	3.06	2.83	.23				
	Std. MP-1		57	1.99	15.83	-				
	RU-1		-	-	2.13	.85				
	KC-1		-	6.86	-	.11				
	100		91	5.61	8.99	.11				
	200		81	5.00	6.57	.17				
	300		40	2.37	4.31	.03				
	R X 0460 - X-05		23	1.31	3.51	.01				
	R X 0471 ✓		9	.75	1.13	.01				
	R X 0483 ✓		80	4.98	7.18	.06				
	Std. MP-1		59	1.90	-	-				
	RU-1		-	-	2.24	.84				
	KC-1		-	6.80	-	.11				
	100		91	5.37	8.92	.11				
	200		83	4.88	6.68	.16				
	300		41	2.29	4.34	.04				

NOTE:

Rejects retained three weeks
Pulps retained three months
unless otherwise arranged.

.....
Registered Assayer, Province of British Columbia



Kamloops Research & Assay Laboratory Ltd.

2095 WEST TRANS CANADA HIGHWAY—KAMLOOPS, B.C. V1S 1A7
TELEPHONE 372-2784 - TELEX 048-8320

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS

CERTIFICATE OF ASSAY

TO Cyprus Anvil Mining Corporation

Certificate No. K-2111

Date July 6, 1979.

I hereby certify that the following are the results of assays made by us upon the herein described Vangorda & DY drill core samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
	Repeats & Standards Cont'd.	Ounces Per Ton	Ounces Per Ton	Percent	Percent	Percent	Percent	Percent	Percent	Percent
	R V 0360 ✓✓✓		25	.95	.64	.46				
	R X 0315 ✓✓✓		14	1.45	2.21	.05				
	Std. MP-1		59	1.83	15.71	-				
	RU-1		-	-	2.11	.85				
	KC-1		-	6.86	-	.11				
	100		95	5.41	8.97	.11				
	200		84	4.86	6.57	.16				
	300		40	2.26	4.35	.04				
	R X 0328 ✓ ob		179	15.34	9.31	.17				
	R X 0334 ✓		23	.91	.92	.50				
	Std. MP-1		58	1.85	16.00	-				
	KC-1		-	6.84	20.07	.10				
	RU-1		-	-	2.18	.86				

NOTE:

Rejects retained three weeks
Pulps retained three months
unless otherwise arranged.

.....
Registered Assayer, Province of British Columbia

GEOCHEMICAL LOG

Kamloops Research and Assay Lab.

<u>From</u>	<u>To</u>	<u>Int.</u>	<u>Samp. No.</u>	<u>Ag/AA GMS/MT</u>	<u>Ag/FA GMS/MT</u>	<u>Pb %</u>	<u>Zn %</u>	<u>Pb+Zn %</u>	<u>S.G.</u>	<u>Cu %</u>	<u>BaO %</u>	<u>Au GMS/MT</u>	<u>Po %</u>	<u>Py %</u>	<u>Unit</u>
395.3	396.3	1.0	305	8.0		0.11	0.05			0.02					4K7/9/8
396.6	398.2	1.6	306	8.0		0.08	0.05			0.04					4K7/9/8
398.2	398.9	0.7	307	10.0		0.22	0.22			0.20					4K7/9/8
527.1	529.0	1.9	311	6.0		0.51	0.91	1.42		0.03					4L7/4/6
529.0	531.0	2.0	312	8.0		0.58	1.08	1.66		0.03					4L7/4/6
531.0	532.0	1.0	313	17.0		1.74	3.04	4.78		TR.					4L7/4/6
532.0	533.0	1.0	314	24.0		2.14	3.16	5.30		0.04					4L7/4/3
533.0	534.9	1.9	315	15.0		1.52	2.20	3.72		0.05					4L7/4/3
534.9	536.7	1.8	316	2.0		0.15	0.32	0.47		TR.					4L7/4/6
542.5	544.1	1.6	317	15.0		0.47	0.87	1.34		0.04					4L7/4/6
586.4	588.2	1.8	459	3.0		0.20	0.36	0.56		0.01					4A4
588.2	589.6	1.4	460	22.0		1.31	3.50	4.81		0.02					4A4
589.6	591.1	1.5	461	23.0		1.38	2.81	4.19		0.02					4A4
591.7	592.3	0.6	462	35.0		1.69	3.85	5.54		0.10					4H1
592.3	594.3	2.0	463	28.0		1.55	3.40	4.95		0.01					4A4/7
594.3	596.1	1.8	464	69.0		4.55	1.66	6.21		0.05					4A4/7
596.1	599.7	3.6	465	5.0		0.44	1.31	1.75		0.01					4A4/5/7
599.7	601.3	1.6	466	5.0		0.35	0.49	0.84		0.01					4A4/5/7
601.3	603.3	2.0	467	17.0		1.26	2.20	3.46		0.02					4A4/5/7
603.3	605.3	2.0	468	9.0		0.80	1.30	2.10		0.01					4A4/5/7-4A4/7
605.3	607.3	2.0	469	7.0		0.43	0.97	1.40		0.01					4A4/7
607.3	609.4	2.1	470	9.0		0.57	0.82	1.39		0.01					4A4/7
609.4	611.1	1.7	471	8.0		0.69	1.17	1.86		0.01					4A4/7
611.1	613.1	2.0	472	7.0		0.50	0.25	0.75		0.03					4A4/7
613.1	614.2	1.1	473	TR.		0.07	0.13	0.20		0.03					4A4/7
614.2	616.6	2.4	474	6.0		0.48	0.87	1.35		0.13					4L7/6/4
616.6	618.1	1.5	475	7.0		0.32	0.75	1.07		0.19					4A4/7
618.1	619.6	1.5	476	15.0		0.59	1.31	1.90		0.27					4A4/7
619.6	620.7	1.1	477	9.0		0.43	0.61	1.04		0.06					4L7/4
620.7	622.0	1.3	478	19.0		1.20	1.33	2.53		0.08					4L7/4

79-X-05

GEOCHEMICAL LOG

Page 2 of 2

<u>From</u>	<u>To</u>	<u>Int.</u>	<u>Samp. No.</u>	<u>Ag/AA GMS/MT</u>	<u>Ag/FA GMS/MT</u>	<u>Pb %</u>	<u>Zn %</u>	<u>Pb+Zn %</u>	<u>S.G.</u>	<u>Cu %</u>	<u>BaO %</u>	<u>Au GMS/MT</u>	<u>Po %</u>	<u>Py %</u>	<u>Unit</u>
623.7	625.4	1.7	479	34.0		2.15	3.19	5.34		0.02					4A4/7
625.4	626.3	1.9	480	51.0		3.57	2.17	5.74		0.02					4A4/7
626.3	627.4	1.1	481	33.0		2.71	1.41	4.12		0.03					4A4/7
632.6	634.0	1.4	482	18.0		1.17	1.94	3.11		0.03					4A4/7/5
634.0	635.9	1.9	483	80.0		5.01	7.15	12.16		0.06					4D0
635.9	636.9	1.0	484	78.0		4.54	8.91	13.45		0.08					4D0

BEST SECTION:

634.0 636.9 2.9 79.3 4.85 7.75 12.60

79-X-06



Kamloops Research & Assay Laboratory Ltd.

2095 WEST TRANS CANADA HIGHWAY-KAMLOOPS, B.C. V1S 1A7
TELEPHONE 372-2784 TELEX 048-8320

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS

CERTIFICATE OF ASSAY

TO Cyprus Anvil Mining Corporation

Certificate No. K-2111

Date July 6, 1979.

Vangorda
drill core

I hereby certify that the following are the results of assays made by us upon the herein described drill core samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		Ounces Per Ton	gm/tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent
V-110-R 21	V 0371		22	1.13	1.14	.24				
22	0372		49	3.03	7.13	.06				
23	0373		31	2.39	3.98	.09				
24	0374		9	.16	.11	.27				
25	0375		16	.34	.12	.22				
26	0376		17	.22	.15	.10				
27	0377		4	.04	.04	.16				
28	0381 x		1	.07	.06	.06				
29	0401		27	2.84	1.42	.16				
30	0402		30	3.41	4.43	.07				
V-119-R 31	0403		34	3.67	4.81	.06				
32	0404		30	3.32	4.71	.04				
33	0405		38	3.50	4.84	.05				
34	0406		33	2.97	3.80	.05				
35	0407		166	6.06	8.64	.22				
36	0408		127	10.22	4.87	.04				
37	0409		166	5.99	8.04	.22				
38	0410		Tr	.14	.42	Tr				
39	0411		3	.15	.45	.01				
40	V 0412		3	.22	.46	.10				

NOTE:

Rejects retained three weeks
Pulps retained three months
unless otherwise arranged.

David J. P. B.
.....
Registered Assayer, Province of British Columbia



Kamloops Research & Assay Laboratory Ltd.

2095 WEST TRANS CANADA HIGHWAY—KAMLOOPS, B.C. V1S 1A7
TELEPHONE 372-2784 · TELEX 048-8320

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS

CERTIFICATE OF ASSAY

TO Cyprus Anvil Mining Corporation

Certificate No. K-2111

Date July 6, 1979.

I hereby certify that the following are the results of assays made by us upon the herein described DY drill core samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		Ounces Per Ton	gm/tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent
DY 05	X 0311		6	.51	.91	.03				
	0312		8	.58	1.08	.03				
	0313		17	1.74	3.04	Tr				
	0314		24	2.14	3.16	.04				
	0315		15	1.52	2.20	.05				
	0316		2	.15	.32	Tr				
	0317		15	.47	.87	.04				
	0318		62	4.08	2.92	.28				
87	0319		101	6.52	8.83	.05				
88	0320		81	7.32	5.50	.08				
DY 06	0321		35	2.77	1.54	.03				
	0322		63	4.62	3.73	.13				
	0323		62	4.63	3.52	.23				
	0324		28	2.01	2.17	.02				
	0325		46	2.77	1.69	.09				
	0326		91	7.47	6.96	.02				
	0327		171	15.96	8.79	.04				
	0328		170	15.29	9.31	.10				
	0329		248	23.76	6.85	.12				
	X 0330		245	21.13	4.59	.07				

NOTE:

Rejects retained three weeks
Pulps retained three months
unless otherwise arranged.

DAB for PGB
Registered Assayer, Province of British Columbia



Kamloops Research & Assay Laboratory Ltd.

2095 WEST TRANS CANADA HIGHWAY—KAMLOOPS, B.C. V1S 1A7
TELEPHONE 372-2784 · TELEX 048-8320

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS

CERTIFICATE OF ASSAY

TO Cyprus Anvil Mining Corporation

K-2111

Certificate No. _____

Date July 6, 1979.

I hereby certify that the following are the results of assays made by us upon the herein described DY drill core samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		Ounces Per Ton	gm/tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent
DY ob 99	X 0331		88	6.25	4.57	.19				
100	0332		98	6.48	8.05	.04				
101	0333		98	6.97	6.78	.06				
102	0334		24	.91	.92	.52				
103	0335		60	4.25	2.35	.28				
104	0336		150	12.06	5.70	.11				
105	0337		62	4.62	3.71	.09				
106	0338		9	.09	.17	.10				
107	0339		75	5.07	4.69	.14				
108	0340		36	1.88	4.60	.03				
109	0341		33	1.81	3.45	.03				
110	0342		23	1.37	2.28	.03				
111	0343		22	.92	1.37	.06				
112	0344		34	2.28	4.14	.03				
113	0345		46	2.61	4.79	.04				
114	0346		33	1.88	3.23	.02				
115	0347		114	9.55	7.41	.08				
116	0348		34	2.48	2.28	.28				
117	0349		29	1.92	1.01	.27				
118	X 0350		8	.18	.21	.35				

NOTE:

Rejects retained three weeks
Pulps retained three months
unless otherwise arranged.

DAB for PGB
.....
Registered Assayer, Province of British Columbia



Kamloops Research & Assay Laboratory Ltd.

2095 WEST TRANS CANADA HIGHWAY—KAMLOOPS, B.C. V1S 1A7
TELEPHONE 372-2784 · TELEX 048-8320

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS

CERTIFICATE OF ASSAY

TO Cyprus Anvil Mining Corporation

Certificate No. K-2112

Date July 6, 1979.

I hereby certify that the following are the results of assays made by us upon the herein described DY drill core samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		Ounces Per Ton	gmi/tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent
Ob 119	X 0379		19	.19	.42	.11				
120	0380		2	.07	.02	.03				
121	0382		5	.12	.11	.07				
122	0383		10	.58	.86	.05				
123	0384		14	.37	.20	.08				
124	0385		38	2.41	2.41	.18				
125	0386		30	1.17	.52	.34				
Ob 126	0387		63	3.61	7.30	.12				
127	0388		19	.71	.41	.21				
128	0389		8	.48	.35	.06				
129	0390		39	2.47	2.23	.20				
130	0391		20	.28	.18	.34				
131	0392		33	1.99	2.45	.26				
132	0393		8	.24	.15	.17				
133	0394		2	.14	.07	.04				
134	0395		7	.31	.10	.11				
135	0396		19	.64	.38	.19				
136	0397		27	1.23	.61	.21				
137	0398		6	.03	.03	.05				
138	X 0399		2	.02	.03	.08				

NOTE:

Rejects retained three weeks
Pulps retained three months
unless otherwise arranged.

DAB for PEB
.....
Registered Assayer, Province of British Columbia



Kamloops Research & Assay Laboratory Ltd.

2095 WEST TRANS CANADA HIGHWAY—KAMLOOPS, B.C. V1S 1A7
TELEPHONE 372-2784 · TELEX 048-8320

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS

CERTIFICATE OF ASSAY

TO Cyprus Anvil Mining Corporation

Certificate No. K-2111

Date July 6, 1979.

I hereby certify that the following are the results of assays made by us upon the herein described DY drill core samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		Ounces Per Ton	gm/tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent
ob 139	X 0400		2	.03	.03	.10				
V-119-R 140	0439		1	.07	.37	.07				
141	0451		29	1.97	3.57	.13				
ob 142	0452		56	3.17	5.01	.19				
ob 143	0453		15	.66	.47	.19				
144	0459		3	.20	.36	.01				
145	0460		22	1.31	3.50	.02				
146	0461		23	1.38	2.81	.02				
147	0462		35	1.69	3.85	.10				
148	0463		28	1.55	3.40	.01				
ob 149	0464		69	4.55	1.66	.05				
150	0465		5	.44	1.31	.01				
151	0466		5	.35	.49	.01				
152	0467		17	1.26	2.20	.02				
153	0468		9	.80	1.30	.01				
154	0469		7	.43	.97	.01				
155	0470		9	.57	.82	.01				
156	0471		8	.69	1.17	.01				
157	0472		7	.50	.25	.03				
158	X 0473		Tr	.07	.13	.03				

NOTE:
Rejects retained three weeks
Pulps retained three months
unless otherwise arranged.

..... DAS for P&G
Registered Assayer, Province of British Columbia



Kamloops Research & Assay Laboratory Ltd.

2095 WEST TRANS CANADA HIGHWAY-KAMLOOPS, B.C. V1S 1A7
TELEPHONE 372-2784 - TELEX 048-8320

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS

2 (F)

CERTIFICATE OF ASSAY

TO Cyprus Anvil Mining Corporation

Certificate No. K-2100

Date June 29, 1979.

I hereby certify that the following are the results of assays made by us upon the herein described DY core samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		Ounces Per Ton	gm/tonne XXXXXXXX XXXXXXXX	Percent	Percent	Percent	Percent	Percent	Percent	Percent
15	X 0305		8	.11	.05	.02				
16	0306		8	.08	.05	.04				
17	0307		9	.23	.21	.19				
18	0308		42	2.97	2.21	.14				
19	0309		61	4.24	3.44	.17				
20	X 0310		88	4.71	4.39	.24				
	X 0307 Repeat		10	.22	.22	.20				
	* Standards:									
	MP-1		59	1.90	-	-				
	100		83	5.44	8.92	.11				
	200		82	4.99	6.68	.16				
	300		41	2.29	4.38	.04				
	RU-1		-	-	2.24	.85				
	* Standards same for both Vangorda and DY core									

05
19-X-06

NOTE:

Rejects retained three weeks
Pulps retained three months
unless otherwise arranged.

c.c. Mr. S. Buziak

R. A. Blendell
.....
Registered Assayer, Province of British Columbia



Kamloops Research & Assay Laboratory Ltd.

2095 WEST TRANS CANADA HIGHWAY-KAMLOOPS, B.C. V1S 1A7
TELEPHONE 372-2784 - TELEX 048-8320

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS

CERTIFICATE OF ASSAY

TO Cyprus Anvil Mining Corporation

K-2111

Certificate No. _____

Date July 6, 1979.

I hereby certify that the following are the results of assays made by us upon the herein described Vangorda & DY drill core samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		Ounces Per Ton	Ounces Per Ton	Percent	Percent	Percent	Percent	Percent	Percent	Percent
<u>Repeats & Standards Cont'd.</u>										
	R X 0399 X 06		2	.04	.02	.07				
	R V 0440 ✓ 119		8	.74	.93	.16				
	Std. MP-1		59	1.91	-	-				
	RU-1		-	-	2.22	.84				
	KC-1		-	6.77	-	.12				
	100		94	5.44	8.85	.11				
	200		82	4.97	6.65	.15				
	300		41	2.29	4.38	.04				
	R X 0340 X 06		33	1.80	4.40	.02				
	R X 0350 ✓		7	.20	.21	.36				
	Std. MP-1		58	1.86	-	-				
	RU-1		-	-	2.20	.85				
	KC-1		-	6.92	-	.11				
	100		95	5.50	8.92	.10				
	200		82	4.90	6.66	.13				
	300		43	2.29	4.36	.04				

NOTE:

Rejects retained three weeks
Pulps retained three months
unless otherwise arranged.

.....
DAB for PAB
.....
Registered Assayer, Province of British Columbia



Kamloops Research & Assay Laboratory Ltd.

2095 WEST TRANS CANADA HIGHWAY—KAMLOOPS, B.C. V1S 1A7
TELEPHONE 372-2784 · TELEX 048-8320

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS

CERTIFICATE OF ASSAY

TO Cyprus Anvil Mining Corporation

Certificate No. K-2111

Date July 6, 1979.

I hereby certify that the following are the results of assays made by us upon the herein described Vangorda & DY drill core samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
	Repeats & Standards Cont'd.	Ounces Per Ton	Ounces Per Ton	Percent	Percent	Percent	Percent	Percent	Percent	Percent
	R V 0360 ✓✓✓		25	.95	.64	.46				
	R X 0315 ✓✓✓		14	1.45	2.21	.05				
	Std. MP-1		59	1.83	15.71	-				
	RU-1		-	-	2.11	.85				
	KC-1		-	6.86	-	.11				
	100		95	5.41	8.97	.11				
	200		84	4.86	6.57	.16				
	300		40	2.26	4.35	.04				
	R-X 0328 ✓✓✓		179	15.34	9.31	.17				
	R X 0334 ✓		23	.91	.92	.50				
	Std. MP-1		58	1.85	16.00	-				
	KC-1		-	6.84	20.07	.10				
	RU-1		-	-	2.18	.86				

NOTE:

Rejects retained three weeks
Pulps retained three months
unless otherwise arranged.

.....
Registered Assayer, Province of British Columbia

GEOCHEMICAL LOG

Kamloops Research and Assay Lab.

<u>From</u>	<u>To</u>	<u>Int.</u>	<u>Samp.</u> <u>No.</u>	<u>Ag/AA</u> <u>GMS/MT</u>	<u>Ag/FA</u> <u>GMS/MT</u>	<u>Pb %</u>	<u>Zn %</u>	<u>Pb+Zn</u> <u>%</u>	<u>S.G.</u>	<u>Cu %</u>	<u>BaO %</u>	<u>Au</u> <u>GMS/MT</u>	<u>Po %</u>	<u>Py %</u>	<u>Hg %</u>	<u>Unit</u>
671.0	672.0	1.0	0308	42.0		2.97	2.21	5.18		0.14						4K7
676.7	677.7	1.0	0309	61.0		4.24	3.44	7.68		0.17						4K7/9
678.1	679.4	1.3	0310	88.0		4.71	4.39	9.10		0.24						4K7 4G8
706.6	708.5	1.9	0318	62.0		4.08	2.92	7.00		0.28						4E8
708.5	710.8	2.3	0319	101.0		6.52	8.83	15.35		0.05						4G0
713.0	714.3	1.3	0320	81.0		7.32	5.50	12.82		0.08						4G1/8
714.3	714.8	0.5	0321	35.0		2.77	1.54	4.31		0.03						4L3
714.8	716.1	1.3	0322	63.0		4.62	3.73	8.35		0.13						4G1/8
716.1	716.7	0.6	0323	62.0		4.63	3.52	8.15		0.23						4D4
716.7	717.4	0.7	0324	28.0		2.01	2.17	4.18		0.02						4G1/4/8
717.4	718.2	0.8	0325	46.0		2.77	1.69	4.46		0.09						4D4/8
718.2	720.2	2.0	0326	91.0		7.47	6.96	14.43		0.02						4G1/4/8
720.2	722.2	2.0	0327	172.0		15.96	8.79	24.75		0.04						4G1/4/8
722.2	724.2	2.0	0328	179.0		15.34	9.31	24.65		0.14						4G1/4/8
724.2	725.7	1.5	0329	248.0		23.76	6.85	30.61		0.12						4G1/4/8
725.7	726.7	1.0	0330	245.0		21.13	4.59	25.72		0.07						4G1/4/8
726.7	728.3	1.6	0331	88.0		6.25	4.57	10.82		0.19						4E4
728.3	730.5	2.2	0332	98.0		6.48	8.05	14.53		0.04						4G0
730.5	732.7	2.2	0333	98.0		6.97	6.78	13.75		0.06						4G0
732.7	734.0	1.3	0334	23.0		0.91	0.92	1.83		0.50						4E0
734.0	735.4	1.4	0335	60.0		4.25	2.35	6.60		0.28						4E0
735.4	737.0	1.6	0336	150.0		4.62	5.70	10.32		0.11						4G4/8
737.0	738.0	1.0	0337	62.0		4.62	3.71	8.33		0.09						4G4/8
738.0	738.5	0.5	0338	9.0		0.09	0.17	0.26		0.10						5D6/9
738.5	739.8	1.3	0339	75.0		5.07	4.69	9.76		0.14						4G0
739.8	741.8	2.0	0340	36.0		1.88	4.60	6.48		0.03						4A0
741.8	743.8	2.0	0341	33.0		1.81	3.45	5.26		0.03						4A0
743.8	745.5	1.7	0342	23.0		1.37	2.28	3.65		0.03						4A0
745.5	747.5	2.0	0343	22.0		0.92	1.37	2.29		0.06						4A7
772.1	774.1	2.0	0344	34.0		2.28	4.14	6.42		0.03						4A4
774.1	776.1	2.0	0345	46.0		2.61	4.79	7.40		0.04						4A4
776.1	777.3	1.2	0346	33.0		1.88	3.23	5.11		0.02						4A4

DY 79-X-06

GEOCHEMICAL LOG

Page 2 of 2

<u>From</u>	<u>To</u>	<u>Int.</u>	<u>Samp.</u> <u>No.</u>	<u>Ag/AA</u> <u>GMS/MT</u>	<u>Ag/FA</u> <u>GMS/MT</u>	<u>Pb %</u>	<u>Zn %</u>	<u>Pb+Zn</u> <u>%</u>	<u>S.G.</u>	<u>Cu %</u>	<u>BaO %</u>	<u>Au</u> <u>GMS/MT</u>	<u>Po %</u>	<u>Py %</u>	<u>Hg %</u>	<u>Unit</u>
782.1	782.8	0.7	0347	114.0		9.55	7.41	16.96		0.08						4G4/8
782.8	783.3	0.5	0348	34.0		2.48	2.28	4.76		0.28						4D4/8
783.3	783.9	0.6	0349	29.0		1.92	1.01	2.93		0.27						4C9
783.9	785.2	1.3	0350	8.0		0.18	0.21	0.39		0.35						4A7/9
785.2	786.4	1.2	0382	5.0		0.12	0.11	0.23		0.07						4L3/7
786.4	788.0	1.0	0383	10.0		0.58	0.86	1.44		0.05						4A0
788.0	788.9	0.9	0384	14.0		0.37	0.20	0.57		0.08						4C0
788.9	790.5	0.6	0385	38.0		2.41	2.41	4.82		0.18						4G0
789.5	790.1	0.6	0386	30.0		1.17	0.52	1.69		0.34						4E8
790.1	790.5	0.4	0387	63.0		3.61	7.30	10.91		0.12						4C8
790.5	791.0	0.5	0388	19.0		0.71	0.41	1.12		0.21						4G0
791.0	791.7	0.7	0389	8.0		0.48	0.35	0.83		0.06						4L7
793.6	794.5	0.9	0390	39.0		2.47	2.23	4.70		0.20						4G0
794.5	796.6	2.1	0391	20.0		0.28	0.18	0.46		0.34						4E8
796.6	797.8	1.2	0392	33.0		1.99	2.45	4.44		0.26						4G8
797.8	799.5	1.7	0393	8.0		0.24	0.15	0.39		0.17						4A0
799.5	800.6	1.1	0394	2.0		0.14	0.07	0.21		0.04						4L3/7
800.6	801.6	1.0	0395	7.0		0.31	0.10	0.41		0.11						4A0
802.9	804.2	1.3	0396	19.0		0.64	0.38	1.02		0.19						4G8/9
804.2	805.7	1.5	0397	27.0		1.23	0.61	1.84		0.21						4G8/9
812.6	814.3	1.7	0398	6.0		0.03	0.03	0.06		0.05						4L6/7
814.3	816.1	1.8	0399	2.0		0.02	0.03	0.05		0.08						4L1/7
816.1	817.9	1.8	0400	2.0		0.01	0.03	0.04		0.10						4L6/7
872.5	873.2	0.7	0379	19.0		0.19	0.42	0.61		0.11						4L7
873.2	874.2	1.0	0380	2.0		0.07	0.02	0.09		0.03						4A0
874.2	875.7	1.5	0381	1.0		0.07	0.06	0.13		0.06						4A0
875.7	878.0	2.3	0451	29.0		1.97	3.57	5.54		0.13						4A4
878.0	878.8	0.8	0452	56.0		3.17	5.01	8.18		0.19						4G0
878.8	879.2	0.4	0453	15.0		0.66	0.47	1.13		0.19						4A0

79-X-07



Kamloops Research & Assay Laboratory Ltd.

2095 WEST TRANS CANADA HIGHWAY-KAMLOOPS, B.C. V1S 1A7
TELEPHONE 372-2784 - TELEX 048-8320

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS

CERTIFICATE OF ASSAY

TO Cyprus Anvil Mining Corporation

Certificate No. K-2135

Date July 18, 1979.

I hereby certify that the following are the results of assays made by us upon the herein described DY drill core samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		Ounces Per Ton	gm/tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent
53	X 0617		28	1.51	3.28	.01				
54	0619		4	.26	.49	Tr				
55	0620		1	.02	.03	Tr				
56	0621		4	.32	.45	Tr				
57	0622		35	1.87	4.55	Tr				
58	0623		39	2.13	5.88	.03				
59	0624		156	6.78	16.2	.13				
60	0625		39	2.17	4.70	.01				
61	0626		75	3.61	7.76	.03				
62	0627		105	6.76	9.52	.15				
63	0628 ✕		5	.37	.77	Tr				
64	0629		80	5.51	10.2	.04				
65	X 0630 ✕		83	4.41	9.85	.05				

DY 07

Tr denotes "trace"

NOTE: c.c. Mr. S. Buziak
Rejects retained three weeks
Pulps retained three months
unless otherwise arranged.

Richard S. Buziak
Registered Assayer, Province of British Columbia

79-X-08



Kamloops Research & Assay Laboratory Ltd.

2095 WEST TRANS CANADA HIGHWAY—KAMLOOPS, B.C. V1S 1A7
TELEPHONE 372-2784 · TELEX 048-8320

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS

CERTIFICATE OF ASSAY

TO Cyprus Anvil Mining Corporation

Certificate No. K-2151

Date July 31, 1979.

I hereby certify that the following are the results of assays made by us upon the herein described DY d.d.core samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		Ounces Per Ton	g/tonne.	Percent	Percent	Percent	Percent	Percent	Percent	Percent
68	X 2857		12	.53	.20	.17				
69	2858		5	.19	.17	.05				
70	2859		5	.24	.10	.02				
71	2860		5	.14	.27	.03				
72	2861		38	2.98	2.57	.19				
73	2862		46	3.71	2.95	.12				
74	2863		8	.45	.16	.06				
75	2864		21	1.49	1.14	.36				
76	2865		24	.36	.36	.48				
77	2866		11	.05	.08	.40				
78	2867		12	.05	.09	.53				
79	2868		13	.17	.07	.38				
80	2869		8	.05	.09	.32				
81	2870		4	.02	.04	.24				
82	2871		22	.92	.67	.64				
83	2872		20	.77	.61	.44				
84	2873		18	.54	1.31	.61				
85	2874		18	.81	2.78	.22				
86	2875		15	.44	.32	.45				
87	X 2876		6	.03	.04	.04				

NOTE:

Rejects retained three weeks
Pulps retained three months
unless otherwise arranged.

.....
Registered Assayer, Province of British Columbia



Kamloops Research & Assay Laboratory Ltd.

2095 WEST TRANS CANADA HIGHWAY—KAMLOOPS, B.C. V1S 1A7
TELEPHONE 372-2784 - TELEX 048-8320

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS

CERTIFICATE OF ASSAY

TO Cyprus Anvil Mining Corporation

Certificate No. K-2151

Date July 31, 1979.

I hereby certify that the following are the results of assays made by us upon the herein described DY d.d. core samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		Ounces Per Ton	g/tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent
88	X 2877		13	.26	.20	.39				
89	2878		15	.26	.38	.43				
90	2879		3	.04	.05	.04				
91	2880		15	.10	.06	.49				
92	2881		14	.10	.09	.60				
93	2882		15	.15	.07	.48				
94	2883		24	1.21	.91	.39				
95	2884		19	.83	.44	.41				
96	2885		21	.89	.60	.39				
97	2886		21	.98	.60	.23				
98	2887		32	.65	.25	.35				
99	2888		12	.43	.60	.21				
100	2889		66	3.73	4.88	.25				
101	2890		35	1.84	1.43	.21				
102	2891		12	.32	.37	.29				
103	2892		28	1.93	2.00	.16				
104	2893		8	.25	.30	.06				
105	2894		10	.53	.28	.10				
106	2895		2	.01	.03	.02				
107	X 2896		4	.09	.08	.02				

DY.08

NOTE:

Rejects retained three weeks
Pulps retained three months
unless otherwise arranged.

.....*R. Blandell*.....
Registered Assayer, Province of British Columbia



Kamloops Research & Assay Laboratory Ltd.

2095 WEST TRANS CANADA HIGHWAY-KAMLOOPS, B.C. V1S 1A7
TELEPHONE 372-2784 - TELEX 048-8320

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS

CERTIFICATE OF ASSAY

TO Cyprus Anvil Mining Corporation

Certificate No. K-2151

Date July 31, 1979.

I hereby certify that the following are the results of assays made by us upon the herein described Vangorda d.d. core samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu			
		Ounces Per Ton	g/tonne	Percent	Percent	Percent	Percent	Percent	Percent
41	V 02936		9	.43	.55	.17			
42	02937		10	.66	1.45	.07			
43	02938		13	.63	2.26	.09			
44	02939		11	.46	1.28	.12			
45	02940		33	2.45	3.58	.27			
46	02941		43	4.14	5.67	.12			
47	02942		67	4.85	6.14	.06			
48	02943		85	4.60	6.84	.05			
49	02944		34	2.03	2.59	.23			
50	02945		20	.99	1.90	.31			
51	02946		22	.99	2.08	.31			
52	02947		9	.22	.45	.35			
53	02948		22	1.51	.36	.25			
54	02949		10	.18	.20	.35			
55	02950		14	.49	.31	.38			
56	02951		14	.59	.46	.29			
57	02952		27	1.90	1.37	.21			
58	02953		11	.63	.67	.12			
59	02970		6	.12	.12	.10			
60	V 02971		35	2.14	5.65	.08			

V-101-R
V-72-R
D1-08
V-72-R

.....*R. S. Rendell*.....
Registered Assayer, Province of British Columbia

NOTE:
Rejects retained three weeks
Pulps retained three months
unless otherwise arranged.



Kamloops Research & Assay Laboratory Ltd.

2095 WEST TRANS CANADA HIGHWAY—KAMLOOPS, B.C. V1S 1A7
TELEPHONE 372-2784 - TELEX 048-8320

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS

CERTIFICATE OF ASSAY

TO Cyprus Anvil Mining Corporation

Certificate No. K-2151

Date July 31, 1979.

I hereby certify that the following are the results of assays made by us upon the herein described DY d.d. core samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		Ounces Per Ton	g/tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent
108	X 2897		2	.02	.04	.02				
109	2898		3	.07	.06	.04				
110	2899		3	.09	.10	.03				
111	2900		18	.92	1.03	.21				
112	2954		57	3.96	4.28	.23				
113	2955		29	1.88	3.60	.10				
114	2956		19	.20	.11	.29				
115	2957		19	.77	.42	.22				
116	2958		20	.55	.20	.20				
117	2959		5	.07	.09	.03				
118	2960		3	.01	.02	.06				
119	2961		6	.30	.53	.04				
120	2962		3	.06	.29	.09				
121	2963		4	.06	.39	.04				
122	2964		4	.08	.28	.08				
123	2965		4	.10	.06	.03				
124	2966		20	.34	.45	.49				
125	2967		1	.01	.01	.03				
126	2968		4	.24	.02	.02				
127	X 2969		30	1.79	1.37	.24				

DY-08

NOTE:

Rejects retained three weeks
Pulps retained three months
unless otherwise arranged.

R. Sandell
.....
Registered Assayer, Province of British Columbia



Kamloops Research & Assay Laboratory Ltd.

2095 WEST TRANS CANADA HIGHWAY-KAMLOOPS, B.C. V1S 1A7
TELEPHONE 372-2784 - TELEX 048-8320

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS

CERTIFICATE OF ASSAY

TO Cyprus Anvil Mining Corporation

Certificate No. K-2151

Date July 31, 1979.

I hereby certify that the following are the results of assays made by us upon the herein described DY d.d. core samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu					
		Ounces Per Ton	g/tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent	
DY-08 128 129 130 131 132 133 134 135	X 2980		16	.82	.39	.33					
	2981		14	.51	.21	.48					
	2982		4	.19	.21	.02					
	2983		5	.13	.11	.22					
	2984		8	.30	.03	.36					
	2985		5	.13	.03	.24					
	2986		11	.38	.76	.11					
	X 2987		5	.04	.02	.02					
	Repeats: X 2889	08		65	3.43	4.45	.24				
	2960	✓		4	.02	.03	.06				
2865	✓		23	.33	.34	.45					
X 2882	✓		14	.15	.08	.46					
Standards:	MP-1		58	1.86	-	-					
	RU-1		6	-	2.22	.79					
	KC-1		-	6.81	-	.11					
	100		93	5.45	9.14	.11					
	200		82	4.86	6.58	.16					
	300		40	2.37	4.21	.04					

NOTE:

Rejects retained three weeks
Pulps retained three months
unless otherwise arranged.

.....
R. Stenwell
Registered Assayer, Province of British Columbia



Kamloops Research & Assay Laboratory Ltd.

2095 WEST TRANS CANADA HIGHWAY-KAMLOOPS, B.C. V1S 1A7
TELEPHONE 372-2784 - TELEX 048-8320

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS

CERTIFICATE OF ASSAY

TO Cyprus Anvil Mining Corporation

Certificate No. K-2163

Date July 31, 1979.

I hereby certify that the following are the results of assays made by us upon the herein described DY drill core samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		Ounces Per Ton	g/tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent
100	X 2979		16	.42	.74	.35				
101	2988		6	.14	1.02	.11				
102	2989		5	.17	.33	.10				
103	2990		3	.05	.43	.02				
104	2991		40	2.50	1.37	.36				
105	2992		24	1.87	1.11	.20				
106	2993		53	4.20	3.60	.19				
107	2994		25	1.56	2.99	.04				
108	2995		86	4.61	5.76	.17				
109	2996		112	4.94	6.34	.15				
110	2997		48	2.64	4.02	.04				
111	2998		38	2.30	3.84	.03				
112	2999		25	1.57	2.40	.04				
113	X 3000		13	.69	.91	.05				

X-08

NOTE:

Rejects retained three weeks
Pulps retained three months
unless otherwise arranged.

.....
R. B. Blundell
Registered Assayer, Province of British Columbia



Kamloops Research & Assay Laboratory Ltd.

2095 WEST TRANS CANADA HIGHWAY-KAMLOOPS, B.C. V1S 1A7
TELEPHONE 372-2784 - TELEX 048-8320

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS

CERTIFICATE OF ASSAY

TO Cyprus Anvil Mining Corporation

Certificate No. K-2163

Date July 31, 1979

I hereby certify that the following are the results of assays made by us upon the herein described Vangorda drill core samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		Ounces Per Ton	g/tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent
21	V 0684		14	.92	1.65	.04				
22	0685		24	1.52	2.53	.03				
23	0686		13	.87	1.79	.08				
24	0687		33	1.93	3.27	.03				
25	0688		21	1.29	2.58	.04				
26	0689		47	2.75	4.25	.06				
27	0690		112	8.60	9.01	.06				
28	0691		98	8.82	12.79	.06				
29	0692		15	.65	2.61	.20				
30	0693		6	.52	.71	.09				
31	0694		56	4.25	2.18	.20				
32	0695		21	1.45	1.25	.42				
33	0696		13	.64	.77	.12				
34	0697		14	.32	.42	1.16				
35	0698		14	.55	1.08	.39				
36	0699		9	.15	.38	.62				
37	0700		9	.12	.32	.76				
38	0701		13	.74	1.35	.04				
39	0702		13	.65	.96	.06				
40	V 0703		3	.03	.03	.02				

V-303-R

X-08

NOTE:

Rejects retained three weeks
Pulps retained three months
unless otherwise arranged.

R. B. Shindler
.....
Registered Assayer, Province of British Columbia



Kamloops Research & Assay Laboratory Ltd.

2095 WEST TRANS CANADA HIGHWAY—KAMLOOPS, B.C. V1S 1A7
TELEPHONE 372-2784 - TELEX 048-8320

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS

3

CERTIFICATE OF ASSAY

TO Cyprus Anvil Mining Corporation

Certificate No. K-2163

Date July 31, 1979.

I hereby certify that the following are the results of assays made by us upon the herein described Vangorda ~~drill core~~ samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		Ounces Per Ton	g/tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent
X-08 41	V 0704		16	.81	.92	.07				
	42	0705	18	.92	1.41	.06				
	43	0706	17	1.21	1.38	.06				
	44	0707	14	.90	2.08	.03				
45	0751		10	.36	.43	.34				
46	0752		12	.64	.65	.27				
47	0753		13	.61	.95	.20				
48	0754		9	.33	.70	.34				
49	0755		11	.30	.36	.31				
50	0756		14	.51	.61	.29				
V-303-R 51	0757		13	.52	1.00	.48				
	52	0758	12	.38	.68	.38				
	53	0759	13	.26	.66	.36				
	54	0760	7	.15	.44	.26				
	55	0761	7	.27	.37	.18				
	56	0762	7	.15	.41	.17				
	57	0763	8	.07	.29	.14				
	58	0764	6	.05	.14	.10				
V-302-R 59	0765		122	8.70	7.66	.18				
	V 0766		63	4.79	5.41	.23				

NOTE:

Rejects retained three weeks
Pulps retained three months
unless otherwise arranged.

R. Blundell

Registered Assayer, Province of British Columbia



Kamloops Research & Assay Laboratory Ltd.

2095 WEST TRANS CANADA HIGHWAY-KAMLOOPS, B.C. V1S 1A7
TELEPHONE 372-2784 - TELEX 048-8320

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS

CERTIFICATE OF ASSAY

TO Cyprus Anvil Mining Corporation,
330 - 355 Burrard St.,
Vancouver, B. C. Attention: Dr. G. Simpson


Certificate No. K-2163
Date July 31, 1979.

I hereby certify that the following are the results of assays made by us upon the herein described Vangorda drill core samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		Ounces Per Ton	g/tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent
301	1 V 0664		10	.53	.43	.12				
	2 0665		15	4.46	.40	.19				
	3 0666		19	1.55	1.70	.12				
	4 0667		15	.61	.55	.25				
5	0668		9	.85	2.02	.05				
6	0669		25	2.84	2.79	.17				
7	0670		3	.17	.10	.02				
8	0671		3	.09	.07	.03				
x-08	9 0672		3	.14	.24	.01				
	10 0673		14	.91	1.46	.26				
11	0674		36	2.51	3.45	.21				
x-08	12 0675		4	.08	.11	.05				
x-08	13 0676		30	2.10	3.27	.09				
V-303-R	14 0677		69	3.73	5.38	.07				
	15 0678		101	7.62	12.60	.06				
	16 0679		12	1.09	.92	.01				
	17 0680		71	5.93	7.79	.12				
	18 0681		14	1.34	2.10	.04				
	19 0682		68	3.63	6.53	.30				
	20 V 0683		37	2.33	4.67	.03				

NOTE:

Rejects retained three weeks
Pulps retained three months
unless otherwise arranged.


.....
Registered Assayer, Province of British Columbia



Kamloops Research & Assay Laboratory Ltd.

2095 WEST TRANS CANADA HIGHWAY—KAMLOOPS, B.C. V1S 1A7
TELEPHONE 372-2784 - TELEX 048-8320

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS

CERTIFICATE OF ASSAY

TO Cyprus Anvil Mining Corporation

Certificate No. K-2163

Date July 31, 1979.

I hereby certify that the following are the results of assays made by us upon the herein described Vangorda drill core samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		Ounces Per Ton	g/tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent
<u>Repeats & Standards</u>										
	R V 0670		3	.18	.10	.02				
	Std. MP-1		58	1.83	-	-				
	RU-1		11	-	2.30	.85				
	KC-1		-	7.09	-	.11				
	100		95	5.43	8.86	.11				
	200		82	5.04	6.85	.16				
	300		40	2.27	4.19	.04				
	R V 0703 X 08		3	.02	.03	.01				
	V 0766 ✓ 302		61	4.59	5.33	.22				
	V 0778 ✓		15	1.69	3.52	.28				
	V 0797 ✓		17	.66	.91	.45				
	2 V 0889 ✓ 306		29	.90	.50	.30				
	V 0803 ✓ 302		15	.77	.38	.08				
	Std. MP-1		58	1.88	-	-				
	RU-1		-	-	2.19	.85				
	KC-1		-	6.93	-	.11				
	100		95	5.47	9.13	.11				
	200		82	4.94	6.67	.16				
	300		40	2.29	4.46	.04				

NOTE:

Rejects retained three weeks
Pulps retained three months
unless otherwise arranged.

.....
R. Blundell
Registered Assayer, Province of British Columbia

GEOCHEMICAL LOG

Kamloops Research & Assay Lab.

From	To	Int.	Samp. No.	Ag/AA GMS/MT	Ag/FA GMS/MT	Pb %	Zn %	Pb+Zn %	S.G.	Cu %	BaO %	Au GMS/MT	Po %	Py %	Hg %	Unit
502.5	503.6	1.1	2857	12.0		0.53	0.20			0.17						4L7,5
503.6	505.5	1.9	2858	5.0		0.19	0.17			0.05						4L7,5
505.5	507.0	1.5	2859	5.0		0.24	0.10			0.02						4L3,7
507.0	508.2	1.2	2860	5.0		0.14	0.27			0.03						4L3,7
508.2	509.5	1.3	2861	38.0		2.98	2.57	5.55		0.19						4D0
509.5	510.6	1.1	2862	46.0		3.71	2.95	6.66		0.12						4G3/4D7
510.6	511.5	0.9	2863	8.0		0.45	0.16	0.61		0.06						4L3,7,4
511.5	513.1	1.6	2864	21.0		1.49	1.14	2.63		0.36						4C8
513.1	515.2	2.1	2865	24.0		0.36	0.36			0.48						4C0
515.2	516.6	1.4	2866	11.0		0.05	0.08			0.40						4C7
516.6	517.9	1.3	2867	12.0		0.05	0.09			0.53						4C7
517.9	518.2	0.3	2868	13.0		0.17	0.07			0.38						5D6
518.2	518.9	0.7	2869	8.0		0.05	0.09			0.32						4C7,8,9
518.9	519.9	1.0	2870	4.0		0.02	0.04			0.24						5D6
519.9	521.4	1.5	2871	22.0		0.92	0.67	1.59		0.64						4D8
521.4	522.5	1.1	2872	20.0		0.77	0.61	1.38		0.44						4D8
522.5	524.5	2.0	2873	18.0		0.54	1.31	1.85		0.61						4C8
524.5	526.5	2.0	2874	18.0		0.81	2.78	3.59		0.22						4C8
526.5	528.5	2.0	2875	15.0		0.44	0.32			0.45						4C8
528.5	529.3	0.8	2876	6.0		0.03	0.04			0.04						4L0
529.3	531.3	2.0	2877	13.0		0.26	0.20			0.39						4C8
531.3	533.3	2.0	2878	15.0		0.26	0.38			0.43						4C8
533.3	535.3	2.0	2879	3.0		0.04	0.05			0.04						4C8
535.3	536.8	1.5	2880	15.0		0.10	0.06			0.49						4C8
536.8	537.4	0.6	2881	14.0		0.10	0.09			0.60						?
537.4	538.6	1.2	2882	15.0		0.15	0.07			0.48						4C8
538.6	539.9	1.3	2883	24.0		1.21	0.91	2.12		0.39						4C0
539.9	541.5	1.6	2884	19.0		0.83	0.44			0.41						4C0
541.5	543.5	2.0	2885	21.0		0.89	0.60			0.39						4C0
543.5	544.4	0.9	2886	21.0		0.98	0.60			0.23						4K1,7
544.4	545.6	1.2	2887	32.0		0.65	0.25			0.35						4C7,8
545.6	547.2	1.6	2888	12.0		0.43	0.60			0.21						4K0
547.2	549.2	2.0	2889	66.0		3.73	4.88	8.61		0.25						4G0
549.2	550.4	1.2	2890	35.0		1.84	1.43	3.27		0.21						4G0

GEOCHEMICAL LOG

DY 79-X-08

Page 2 of 4

From	To	Int.	Samp. No.	Ag/AA GMS/MT	Ag/FA GMS/MT	Pb %	Zn %	Pb+Zn %	S.G.	Cu %	BaO %	Au GMS/MT	Po %	Py %	Hg %	Unit
550.4	551.3	0.9	2891	12.0		0.32	0.37			0.29						4C8/4G8
551.3	552.0	0.7	2892	28.0		1.93	2.00	3.93		0.16						4C8
552.0	554.0	2.0	2893	8.0		0.25	0.30			0.06						4L7,4
554.0	555.5	1.5	2894	10.0		0.53	0.28			0.10						4L7/4L2,7,8
558.0	560.0	2.0	2895	2.0		0.01	0.03			0.02						4L7
560.0	562.0	2.0	2896	4.0		0.09	0.08			0.02						4L7
562.0	564.0	2.0	2897	2.0		0.02	0.04			0.02						4L7
564.0	566.0	2.0	2898	3.0		0.07	0.06			0.04						4L7
566.0	566.7	0.7	2899	3.0		0.09	0.10			0.03						4L7
566.7	567.1	0.4	2900	18.0		0.92	1.03	1.95		0.21						4H0
567.1	568.1	1.0	2951	14.0		0.59	0.46	1.05		0.29						4L7/4L1,7
568.1	569.0	0.9	2952	27.0		1.90	1.37	3.27		0.21						4D8
569.0	569.5	0.5	2953	11.0		0.63	0.67	1.30		0.12						4L1,2,7
569.5	572.0	2.5	2954	57.0		3.96	4.28	8.24		0.23						4G4,8
572.0	573.2	1.2	2955	29.0		1.88	3.60	5.48		0.10						4A4/4A0
573.2	574.2	1.0	2956	19.0		0.20	0.11			0.29						4K1/4E0
574.2	576.2	2.0	2957	19.0		0.77	0.42			0.22						4A0/4C7
576.2	577.7	1.5	2958	20.0		0.55	0.20			0.20						4C7
577.7	579.7	2.0	2959	5.0		0.07	0.09			0.03						5A7,9/5A1
579.7	581.9	2.2	2960	3.0		0.01	0.02			0.06						4L7
586.6	588.3	1.7	2961	6.0		0.30	0.53			0.04						4A0
588.3	588.7	0.4	2962	3.0		0.06	0.29			0.09						4L2,7
588.7	589.1	0.4	2963	4.0		0.06	0.39			0.04						4A0
589.1	592.4	3.3	2964	4.0		0.08	0.28			0.08						4C7
592.4	592.9	0.5	2965	4.0		0.10	0.06			0.03						4A0
592.9	593.8	0.9	2966	20.0		0.34	0.45			0.49						4L6,7
593.8	595.8	2.0	2967	1.0		0.01	0.01			0.03						4L7/4L6,7
595.8	597.2	1.4	2968	4.0		0.24	0.02			0.02						4L6,7
597.2	597.5	0.3	2969	30.0		1.79	1.37	3.16		0.24						4C0
597.5	598.0	0.5	2979	16.0		0.42	0.74			0.35						4K0
598.0	599.2	1.2	2980	16.0		0.82	0.39			0.33						4K0

GEOCHEMICAL LOG

DY 79-X-08

Page 3 of 4

<u>From</u>	<u>To</u>	<u>Int.</u>	<u>Samp. No.</u>	<u>Ag/AA GMS/MT</u>	<u>Ag/FA GMS/MT</u>	<u>Pb %</u>	<u>Zn %</u>	<u>Pb+Zn %</u>	<u>S.G.</u>	<u>Cu %</u>	<u>BaO %</u>	<u>Au GMS/MT</u>	<u>Po %</u>	<u>Py %</u>	<u>Hg %</u>	<u>Unit</u>
599.2	600.2	1.0	2981	14.0		0.51	0.21			0.48						4E0
600.2	602.3	2.1	2982	4.0		0.19	0.21			0.02						4L0
602.3	605.3	3.0	2983	5.0		0.13	0.11			0.22						4L0
605.3	606.2	0.9	2984	8.0		0.30	0.03			0.36						4C7
606.2	608.0	1.8	2985	5.0		0.13	0.03			0.24						4L7
608.0	610.2	2.2	2986	11.0		0.38	0.76			0.11						4C7
610.2	610.8	0.6	2987	5.0		0.04	0.02			0.02						4A0
616.2	617.8	1.6	2988	6.0		0.14	1.02			0.11						4C7,8
617.8	618.8	1.0	2989	5.0		0.17	0.33			0.10						4C7,8
618.8	620.5	1.7	2990	3.0		0.05	0.43			0.02						4L6,5
620.5	622.0	1.5	2991	40.0		2.50	1.37	3.87		0.36						4E8,7
622.0	623.3	1.3	2992	24.0		1.87	1.11	2.98		0.20						4E8,7
623.3	624.6	1.3	2993	53.0		4.20	3.60	7.80		0.19						4G8
675.2	676.3	1.1	2994	25.0		1.56	2.99	4.55		0.04						4A4
676.3	677.7	1.4	2995	86.0		4.61	5.76	10.37		0.17						4G0
677.7	679.1	1.4	2996	112.0		4.94	6.34	11.28		0.15						4G0
679.1	680.5	1.4	2997	48.0		2.64	4.02	6.66		0.04						4A4
680.5	681.5	1.0	2998	38.0		2.30	3.84	6.14		0.03						4A4
681.5	683.5	2.0	2999	25.0		1.57	2.40	3.97		0.04						4A0
683.5	685.5	2.0	3000	13.0		0.69	0.91	1.60		0.05						4A0
685.5	687.5	2.0	701	13.0		0.74	1.35	2.09		0.04						4A0
687.5	689.1	1.6	702	13.0		0.65	0.96	1.61		0.06						4A0
689.1	689.4	0.3	703	3.0		0.03	0.03	0.06		0.02						5D6
689.4	691.0	1.6	704	16.0		0.81	0.92	1.73		0.07						4A0
691.0	692.9	1.9	705	18.0		0.92	1.41	2.33		0.06						4A0
692.9	695.1	2.2	706	17.0		1.21	1.38	2.59		0.06						4L1,7
695.1	696.6	1.5	707	14.0		0.90	2.08	2.98		0.03						4A0

79-X-09



Kamloops Research & Assay Laboratory Ltd.

2095 WEST TRANS CANADA HIGHWAY—KAMLOOPS, B.C. V1S 1A7
TELEPHONE 372-2784 - TELEX 048-8320

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS

CERTIFICATE OF ASSAY

TO Cyprus Anvil Mining Corporation,
330 - 355 Burrard St.,
Vancouver, B. C. V6C 2G8

Attention: Dr. G. Simpson

Certificate No. K-2171

Date August 4, 1979.

I hereby certify that the following are the results of assays made by us upon the herein described DY drill core samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		Ounces Per Ton	g/tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent
X-09 1	X 0806		3	.01	.01	.01				
2	0807		3	.02	.01	.02				
3	0808		12	.05	.01	.24				
4	0809		7	.03	L .01	.32				
5	0810		13	.09	.03	.32				
6	0811		14	.31	.23	.35				
7	0812		14	.43	.29	.31				
8	0813		7	.05	.01	.19				
9	0814		7	.04	.01	.20				
10	0815		4	.03	.01	.13				
11	0816		3	.03	.02	.02				
12	0817		4	.02	.02	.02				
13	0818		4	.02	.01	.02				
14	0819		6	.09	.05	.01				
15	0820		5	.03	.01	.04				
16	0821		4	.03	.02	.01				
17	0822		11	.07	.09	.01				
18	0823		7	.13	.09	.01				
19	0824		14	.13	.05	.02				
20	X 0825		17	.83	1.26	.02				

NOTE: L = "less than"
Rejects retained three weeks
Pulps retained three months
unless otherwise arranged.

B. B. Blendell
.....
Registered Assayer, Province of British Columbia



Kamloops Research & Assay Laboratory Ltd.

2095 WEST TRANS CANADA HIGHWAY-KAMLOOPS, B.C. V1S 1A7
TELEPHONE 372-2784 - TELEX 048-8320

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS

CERTIFICATE OF ASSAY

TO Cyprus Anvil Mining Corporation

Certificate No. K-2171

Date August 4, 1979.

I hereby certify that the following are the results of assays made by us upon the herein described DY drill core samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		Ounces Per Ton	g/tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent
X-09 21	X 0826		23	1.17	1.36	.03				
22	0827		4	.08	.06	.01				
23	0828		28	1.40	1.78	.06				
24	0829		14	.68	.68	.16				
25	X 0830		19	1.51	4.92	.04				
Repeats & Standards:										
	RX0811		14	.32	.25	.36				
	RX0827		4	.08	.06	.01				
	Std. MP-1		-	1.88	-	-				
	RU-1		7	-	2.14	-				
	100		95	5.29	-	.095				
	200		82	4.91	6.74	-				
	300		40	2.26	4.27	.032				

NOTE:

Rejects retained three weeks
Pulps retained three months
unless otherwise arranged.

R. Blundell
.....
Registered Assayer, Province of British Columbia



Kamloops Research & Assay Laboratory Ltd.

2095 WEST TRANS CANADA HIGHWAY—KAMLOOPS, B.C. V1S 1A7
TELEPHONE 372-2784 · TELEX 048-8320

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS

CERTIFICATE OF ASSAY

TO Cyprus Anvil Mining Corporation

Certificate No. K-2182

Date August 10, 1979.

I hereby certify that the following are the results of assays made by us upon the herein described DY drill core samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		Ounces Per Ton	g/tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent
X-09 86	X 0708		23	1.77	1.59	.05				
87	0709		22	1.46	1.55	.09				
88	0710		18	1.33	2.05	.05				
89	0711		38	2.15	6.04	.01				
90	0712		23	1.35	3.32	.01				
91	0713		48	2.32	6.32	.04				
92	0714		7	.39	1.07	.01				
93	0715		6	.27	.83	.01				
94	0716		3	.16	.69	.01				
95	0717		8	.19	.38	.01				
96	0718		14	.69	1.81	.02				
97	0719		6	.34	1.28	.02				
98	0720		11	.56	1.13	.06				
99	0721		5	.23	.27	.04				
100	0722		28	1.55	1.58	.07				
101	0723		58	3.78	5.51	.03				
102	0724		51	3.55	5.72	.06				
103	0725		46	4.52	4.76	.23				
104	0726		51	3.55	4.03	.10				
105	X 0727		24	1.47	2.76	.09				

NOTE:
Rejects retained three weeks
Pulps retained three months
unless otherwise arranged.

R. B. ...
.....
Registered Assayer, Province of British Columbia



Kamloops Research & Assay Laboratory Ltd.

2095 WEST TRANS CANADA HIGHWAY-KAMLOOPS, B.C. V1S 1A7
TELEPHONE 372-2784 - TELEX 048-8320

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS

7

CERTIFICATE OF ASSAY

TO Cyprus Anvil Mining Corporation

Certificate No. K-2182

Date August 10, 1979.

I hereby certify that the following are the results of assays made by us upon the herein described DY drill core samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		Ounces Per Ton	g/tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent
X-09 106	X 0728		56	3.33	5.62	.08				
107	0729		26	1.29	2.23	.11				
108	0730		13	.59	.81	.14				
109	0731		35	2.36	2.28	.12				
110	0732		19	.65	.87	.38				
111	0733		40	2.55	4.23	.14				
112	0734		6	.37	.82	.04				
113	0735		49	3.06	4.39	.04				
114	0736		35	2.16	6.89	.02				
115	0831		32	1.63	4.75	.01				
116	0832		30	1.82	3.64	.02				
117	0833		33	1.89	4.77	.02				
118	0834		26	1.24	2.76	.03				
119	0836		11	1.02	.79	.10				
120	0837		11	.89	2.01	.07				
121	0838		9	.49	2.65	.08				
122	0839		2	.05	.10	.02				
123	0840		17	1.00	2.83	.08				
124	0841		14	.82	2.68	.08				
125	X 0842		23	1.56	4.09	.07				

NOTE:

Rejects retained three weeks
Pulps retained three months
unless otherwise arranged.

.....
R. S. Sundeel
Registered Assayer, Province of British Columbia



Kamloops Research & Assay Laboratory Ltd.

2095 WEST TRANS CANADA HIGHWAY—KAMLOOPS, B.C. V1S 1A7
TELEPHONE 372-2784 TELEX 048-8320

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS

CERTIFICATE OF ASSAY

TO Cyprus Anvil Mining Corporation

Certificate No. K-2182

Date August 10, 1979.

I hereby certify that the following are the results of assays made by us upon the herein described DY drill core samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		Ounces Per Ton	g/tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent
126	X 0843		34	2.31	5.15	.05				
127	0844		16	1.00	2.65	.06				
128	0845		5	.23	.35	.05				
129	0846		3	.09	.23	.02				
X-09 130	0847		7	.40	1.53	.06				
131	0848		26	1.60	4.54	.07				
132	0849		52	3.52	3.94	.08				
133	0850		24	1.54	1.37	.06				
134	0858		76	4.56	6.12	.06				
135	0859		22	2.65	2.53	.02				
V-305 136	0860		25	1.70	3.09	.02				
137	X 0861		60	4.26	6.61	.05				
	Repeats:									
	X 0723 09		55	3.58	5.38	.03				
	0847 09		7	.40	1.45	.05				
	0833 09		32	2.11	4.75	.03				
	0729 09		27	1.26	2.34	.11				
	X 0850 09		25	1.54	1.40	.06				

NOTE:

Rejects retained three weeks
Pulps retained three months
unless otherwise arranged.

.....
R. S. Stoddell
Registered Assayer, Province of British Columbia



Kamloops Research & Assay Laboratory Ltd.

2095 WEST TRANS CANADA HIGHWAY-KAMLOOPS, B.C. V1S 1A7
TELEPHONE 372-2784 - TELEX 048-8320

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS

CERTIFICATE OF ASSAY

TO Cyprus Anvil Mining Corporation

Certificate No. K-2182

Date August 10, 1979.

I hereby certify that the following are the results of assays made by us upon the herein described DY drill core samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		Ounces Per Ton	g/tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent
	Standards:									
	MP-1		58	1.88	16.61	2.09				
	RU-1		-	-	2.29	.85				
	KC-1		-	7.29	20.36	.114				
	100		95	5.51	9.09	.103				
	200		82	4.89	6.52	.155				
	300		40	2.31	4.32	.04				
X-09										

NOTE:

Rejects retained three weeks
Pulps retained three months
unless otherwise arranged.

c.c. Mr. S. Buziak

R. Blundell
.....
Registered Assayer, Province of British Columbia

GEOCHEMICAL LOG

Kamloops Research and Assay Lab.

<u>From</u>	<u>To</u>	<u>Int.</u>	<u>Samp. No.</u>	<u>Ag/AA GMS/MT</u>	<u>Ag/FA GMS/MT</u>	<u>Pb %</u>	<u>Zn %</u>	<u>Pb+Zn %</u>	<u>S.G.</u>	<u>Cu %</u>	<u>BaO %</u>	<u>Au GMS/MT</u>	<u>Po %</u>	<u>Py %</u>	<u>Hg %</u>	<u>Unit</u>
502.6	504.6	2.0	806	3.0		0.01	0.01			0.01						4L3
504.6	506.8	2.2	807	3.0		0.02	0.01			0.02						4L3
506.8	509.1	2.3	808	12.0		0.05	0.01			0.24						4K0
509.1	510.4	1.3	809	7.0		0.03	0.01(L)			0.32						4K0
510.4	510.9	0.5	810	13.0		0.09	0.03			0.32						4K8
510.9	511.6	0.7	811	14.0		0.32	0.25			0.36						4K0
511.6	513.6	2.0	812	14.0		0.43	0.29			0.31						4K0
513.6	514.6	1.0	813	7.0		0.05	0.01			0.19						4K0
514.6	515.6	1.0	814	7.0		0.04	0.01			0.20						4C0
515.6	517.6	2.0	815	4.0		0.03	0.01			0.13						4A0
517.6	519.6	2.0	816	3.0		0.03	0.02			0.02						4A0
519.6	521.6	2.0	817	4.0		0.02	0.02			0.02						4A0
521.6	522.2	0.6	818	4.0		0.02	0.01			0.02						4A0
522.2	523.6	1.4	819	6.0		0.09	0.05			0.01						4C0
523.6	525.0	1.4	820	5.0		0.03	0.01			0.04						4A0
525.0	525.6	0.6	821	4.0		0.03	0.02			0.01						4C0
525.6	526.4	0.8	822	11.0		0.07	0.09			0.01						4K0
526.4	527.6	1.2	823	7.0		0.13	0.09			0.01						4C0
527.6	528.8	1.2	824	14.0		0.13	0.05			0.02						4K0
528.8	530.0	1.2	825	17.0		0.83	1.26	2.09		0.02						4A1
530.0	531.2	1.2	826	23.0		1.17	1.36	2.53		0.02						4A1
531.2	532.5	1.3	827	4.0		0.08	0.06	0.14		0.01						4C0
532.5	534.1	1.6	828	28.0		1.40	1.78	3.18		0.06						4A0
534.1	535.9	1.8	829	14.0		0.68	0.68	1.36		0.16						4L6/2/7/8/9/5
535.9	536.2	0.3	830	19.0		1.51	4.92	6.43		0.04						4A4
580.2	582.2	2.0	831	32.0		1.63	4.75	6.38		0.01						4A4
582.2	584.2	2.0	832	30.0		1.82	3.64	5.46		0.02						4A4
584.2	586.2	2.0	833	33.0		1.89	4.77	6.66		0.02						4A4
586.2	587.6	1.4	834	26.0		1.24	2.76	4.00		0.03						4A4
			835	(no sample)												
592.8	595.0	2.2	836	11.0		1.02	0.79	1.81		0.10						4A0
595.0	597.2	2.2	837	11.0		0.89	2.01	2.90		0.07						4L6/9
597.2	597.9	0.7	838	9.0		0.49	2.65	3.14		0.08						4A0

(L) Less than

GEOCHEMICAL LOG

79-X-09

Page 2 of 3

From	To	Int.	Samp. No.	Ag/AA GMS/MT	Ag/FA GMS/MT	Pb %	Zn %	Pb+Zn %	S.G.	Cu %	BaO %	Au GMS/MT	Po %	Py %	Hg %	Unit
597.9	598.1	0.2	839	2.0		0.05	0.10	0.15		0.02						5D3
598.1	600.3	2.2	840	17.0		1.00	2.83	3.83		0.08						?
600.3	602.5	2.2	841	15.0		0.82	2.68	3.50		0.08						4A0
602.5	604.5	2.0	842	23.0		1.56	4.09	5.65		0.07						4L7
604.5	606.0	1.5	843	34.0		2.31	5.15	7.46		0.05						4L7
606.0	607.7	1.7	844	16.0		1.00	2.65	3.65		0.06						4L4
607.7	609.1	1.4	845	5.0		0.23	0.35	0.58		0.05						4A0
609.1	609.9	0.8	846	3.0		0.09	0.23	0.32		0.02						5D3
609.9	611.3	1.4	847	7.0		0.40	1.53	1.93		0.06						4L4/7
611.3	612.6	1.3	848	26.0		1.60	4.54	6.14		0.07						4D1
612.6	614.6	2.0	849	52.0		3.53	3.94	7.47		0.08						4L1/4
614.6	616.6	2.0	850	24.0		1.54	1.37	2.91		0.06						4L1/4
616.6	618.3	1.7	708	23.0		1.77	1.59	3.36		0.05						4L1/4
618.3	620.3	2.0	709	22.0		1.46	1.55	3.01		0.09						4D1/4
620.3	622.0	1.7	710	18.0		1.33	2.05	3.38		0.05						4D1/4
622.0	622.7	0.7	711	38.0		2.15	6.04	8.19		0.01						4D1/4
622.7	623.1	0.4	712	23.0		1.35	3.32	4.67		0.01						5D3
623.1	624.1	1.0	713	48.0		2.32	6.32	8.64		0.04						4L1/4
624.1	625.6	1.5	714	7.0		0.39	1.07	1.46		0.01						5D3
625.6	627.2	1.6	715	6.0		0.27	0.83	1.10		0.01						4L6
627.2	627.8	0.6	716	3.0		0.16	0.69	0.85		0.01						4L4
627.8	629.7	1.9	717	8.0		0.19	0.38	0.57		0.01						5D3/5A1
629.7	630.2	0.5	718	14.0		0.69	1.81	2.50		0.02						4L1/4/7
630.2	632.0	1.8	719	6.0		0.34	1.28	1.62		0.02						4A7
632.0	634.0	2.0	720	11.0		0.56	1.13	1.69		0.06						4A0
634.0	636.0	2.0	721	5.0		0.23	0.27	0.50		0.04						4A0
636.0	636.8	0.8	722	28.0		1.55	1.58	3.13		0.07						4A0
636.8	638.8	2.0	723	58.0		3.78	5.51	9.29		0.03						4A4
638.8	640.1	1.3	724	51.0		3.55	5.72	9.27		0.06						4A4
640.1	640.9	0.8	725	46.0		4.52	4.76	9.28		0.23						4D0
640.9	642.9	2.0	726	51.0		3.55	4.03	7.58		0.10						4D1
642.9	644.9	2.0	727	24.0		1.47	2.76	4.23		0.08						4D1
644.9	646.9	2.0	728	56.0		3.33	5.62	8.95		0.09						4D1
646.9	648.4	1.5	729	26.0		1.29	2.23	3.52		0.11						4D1
648.4	649.2	0.8	730	13.0		0.59	0.81	1.40		0.14						4C0

79-X-11



Kamloops Research & Assay Laboratory Ltd.

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS, B.C. V1S 1A7
TELEPHONE 372-2784 TELEX 048-8320

CERTIFICATE OF ASSAY

TO Cyprus Anvil Mining Corporation

Certificate No. K-2260

Date September 13, 1979.

I hereby certify that the following are the results of assays made by us upon the herein described DY core samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		Ounces Per Ton	g/tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent
22	X 1284		3	.09	.19	.15				
23	1285		2	.05	.01	.03				
24	1286		3	.18	.08	.02				
25	1287		7	.35	.27	.11				
26	1288		28	1.77	2.04	.27				
27	1289		25	1.84	2.12	.21				
28	1290		10	.67	.94	.21				
29	1291		7	.58	.84	.22				
30	1292		12	.91	1.37	.15				
31	1293		7	.38	.66	.08				
72-X-06	32	1315	4	.28	.36	.16				
77-X-08	33	1316	10	.55	2.56	.03				
	34	1317	1	.06	.18	.02				
	35	1318	9	.57	2.66	.06				
	36	1319	Tr	.12	.43	.01				
78-X-02	37	1320	7	.32	.31	.05				
	38	1321	6	.14	.09	.08				
	39	1322	18	.44	.27	.37				
	40	1323	11	.08	.03	.38				
79-X-12	41	X 1324	45	4.16	4.36	.20				

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.

Tr denotes "trace"

DAB for PAB
Registered Assayer, Province of British Columbia



Kamloops Research & Assay Laboratory Ltd.

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS, B.C. V1S 1A7
TELEPHONE 372-2784 TELEX 048-8320

CERTIFICATE OF ASSAY

TO Cyprus Anvil Mining Corporation

Certificate No. K-2260

Date September 13, 1979.

I hereby certify that the following are the results of assays made by us upon the herein described DY core samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		Ounces Per Ton	g/tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent
	Repeats:									
19-x-11	X 1288		29	1.75	2.02	.26				
17-x-08	X 1318		10	.57	2.64	.06				

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.

c.c. Mr. Darryl Hanson

DAB for PAB
Registered Assayer, Province of British Columbia



Kamloops Research & Assay Laboratory Ltd.

2095 WEST TRANS CANADA HIGHWAY-KAMLOOPS, B.C. V1S 1A7
TELEPHONE 372-2784 - TELEX 048-8320

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS

CERTIFICATE OF ASSAY

TO Cyprus Anvil Mining Corporation

Certificate No. K-2244

Date September 6, 1979.

Vangorda
drill core samples

I hereby certify that the following are the results of assays made by us upon the herein described drill core samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		Ounces Per Ton	g/tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent
21	V 1263		33	1.20	1.11	.48				
22	1264		95	6.02	6.27	.08				
23	1265		71	5.44	5.21	.09				
24	1266		35	3.23	2.16	.19				
25	1267		34	2.53	3.36	.51				
26	1268		28	1.77	3.48	.22				
27	1269		34	2.35	5.46	.19				
1-57-R 28	1301		11	.43	.99	.13				
29	1302		103	6.36	6.14	.19				
V-28-R 30	1303		4	.37	.56	.06				
31	1304		51	6.46	5.50	.16				
32	1305		10	.50	.82	.07				
33	1306		49	4.77	6.75	.23				
34	1307		17	1.28	1.42	.43				
35	1308		10	.34	.36	.34				
36	1309		13	.44	.74	.22				
37	1310		10	.22	.26	.30				
38	1311		2	.03	.02	.01				
39	1312		7	.05	.01	.25				
40	1313		8	.05	.01	.32				
41	V 1314		9	.04	.01	.32				

NOTE:
Rejects retained three weeks
Pulps retained three months
unless otherwise arranged.

Robert Deell
.....
Registered Assayer, Province of British Columbia



Kamloops Research & Assay Laboratory Ltd.

2095 WEST TRANS CANADA HIGHWAY—KAMLOOPS, B.C. V1S 1A7
TELEPHONE 372-2784 TELEX 048-8320

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS

CERTIFICATE OF ASSAY

TO Cyprus Anvil Mining Corporation

Certificate No. K-2244

Date September 6, 1979.

I hereby certify that the following are the results of assays made by us upon the herein described DY drill core samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		Ounces Per Ton	g/tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent
42	X 1135		109	6.30	8.30	.27				
43	1136		16	1.01	.67	.39				
44	1137		15	1.41	.95	.24				
45	1138		34	6.50	.93	.26				
46	1139		100	7.78	6.44	.10				
47	1140		52	3.73	2.97	.16				
48	1141		95	7.07	5.80	.08				
49	1142		74	6.86	3.12	.29				
50	1143		97	6.12	6.66	.11				
51	1144		25	1.37	.99	.32				
52	1145		14	.34	.29	.35				
53	1146		18	1.15	.83	.42				
54	1147		315	12.35	6.50	.06				
55	1148		31	2.60	4.47	.04				
56	1149		79	7.00	5.84	.10				
57	1150		84	5.40	5.80	.06				
58	1227		8	.42	.23	.25				
59	1228		32	2.74	1.79	.48				
60	X 1129		5	.73	.51	.05				

NOTE:

Rejects retained three weeks
Pulps retained three months
unless otherwise arranged.

Robert Blundell
Registered Assayer, Province of British Columbia



Kamloops Research & Assay Laboratory Ltd.

2095 WEST TRANS CANADA HIGHWAY-KAMLOOPS, B.C. V1S 1A7
 TELEPHONE 372-2784 - TELEX 048-8320

B.C. LICENSED ASSAYERS
 GEOCHEMICAL ANALYSTS

CERTIFICATE OF ASSAY

TO Cyprus Anvil Mining Corporation

K-2244

Certificate No. _____

Date September 6, 1979.

I hereby certify that the following are the results of assays made by us upon the herein described DY drill core samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		Ounces Per Ton	g/tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent
61	X 1230		1	.18	.14	.04				
62	1231		28	1.69	1.70	.35				
63	1232		22	1.00	1.03	.36				
64	1233		9	.63	1.07	.08				
65	1234		8	.63	.75	.08				
66	1235		Tr	.03	.04	.07				
67	1236		21	1.43	.70	.28				
68	1237		5	.22	.15	.43				
69	1238		6	.15	.10	.35				
70	1239		9	.20	.36	.47				
71	1240		12	.39	1.22	.48				
72	1241		9	.15	.19	.22				
73	1242		27	1.77	2.18	.17				
74	1270		13	.63	.77	.39				
75	1271		4	.06	.06	.06				
76	1272		2	.02	.10	.01				
77	1273		6	.32	.21	.09				
78	1274		34	2.60	1.44	.21				
79	1275		3	.08	.09	.03				
80	X 1276		4	.05	.06	.05				

DY
79-X-12

DY
79-X-11

NOTE:
 Rejects retained three weeks
 Pulps retained three months
 unless otherwise arranged.

.....
 Registered Assayer, Province of British Columbia



Kamloops Research & Assay Laboratory Ltd.

2095 WEST TRANS CANADA HIGHWAY—KAMLOOPS, B.C. V1S 1A7
TELEPHONE 372-2784 · TELEX 048-8320

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS

CERTIFICATE OF ASSAY

TO Cyprus Anvil Mining Corporation

Certificate No. K-2244

Date September 6, 1979.

I hereby certify that the following are the results of assays made by us upon the herein described DY drill core samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		Ounces Per Ton	g/tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent
81	X 1277		5	.11	.08	.10				
82	1278		7	.32	.02	.03				
83	1279		6	.30	.14	.16				
84	1280		30	1.80	2.35	.10				
85	1281		23	1.59	4.15	.02				
86	1282		29	2.16	4.17	.03				
87	X 1283		49	3.35	6.41	.05				
	Repeats:									
	X 1236		21	1.43	.70	.27				
	X 1238		6	.14	.10	.36				
	X 1142		77	6.88	.26	.30				
	Standards:									
	MP-1		58	1.74	15.66	2.11				
	RU-1		7	-	2.29	.89				
	100		95	5.58	8.89	.10				
	200		82	4.53	5.86	.15				
	300		40	2.29	4.25	.03				

NOTE:

Rejects retained three weeks
Pulps retained three months
unless otherwise arranged.

c.c. Mr. Darryl Hanson

.....*R. Blum*.....
Registered Assayer, Province of British Columbia

CYPRUS ANVIL MINING CORPORATION

DY 79-X-11

GEOCHEMICAL LOG

Kamloops Research and Assay Lab.

<u>From</u>	<u>To</u>	<u>Int.</u>	<u>Samp. No.</u>	<u>Ag/AA GMS/MT</u>	<u>Ag/FA GMS/MT</u>	<u>Pb %</u>	<u>Zn %</u>	<u>Pb+Zn %</u>	<u>S.G.</u>	<u>Cu %</u>	<u>BaO %</u>	<u>Au GMS/MT</u>	<u>Po %</u>	<u>Py %</u>	<u>Hg %</u>	<u>Unit</u>
742.1	742.6	0.5	1135	109.0		6.30	8.30	14.60		0.27						
742.6	743.3	0.7	1136	16.0		1.01	0.67	1.68		0.39						4G4,9 4C9
745.6	747.7	2.1	1137	15.0		1.41	0.95	2.36		0.24						4K9
747.7	749.7	2.0	1138	34.0		6.50	0.93	7.43		0.26						4K8,9
749.7	750.9	1.2	1139	100.0		7.78	6.44	14.22		0.10						4G4,8,9
750.9	751.5	0.6	1140	52.0		3.73	2.97	6.70		0.16						4K8
751.5	753.0	1.5	1141	95.0		7.07	5.80	12.87		0.08						4G4,8
753.0	754.0	1.0	1142	74.0		6.86	3.12	9.98		0.29						4K8,9
754.0	755.4	1.4	1143	97.0		6.12	6.66	12.78		0.11						4G4,8,3
755.4	757.2	1.8	1144	25.0		1.37	0.99	2.36		0.32						4K8
757.5	759.3	1.8	1145	14.0		0.34	0.29	0.63		0.35						4K9,8,1
759.3	761.1	1.8	1146	18.0		1.15	0.83	1.98		0.42						4K9,8,1
761.1	762.1	1.0	1147	315.0		12.35	6.50	18.85		0.06						4J4,8
762.1	762.7	0.6	1148	31.0		2.60	4.47	7.07		0.04						4G4,8
762.7	763.5	0.8	1149	79.0		7.00	5.84	12.84		0.10						4D8,7
763.5	765.5	2.0	1150	84.0		5.40	5.80	11.20		0.06						4G4,8,3
765.5	767.1	1.6	1251	81.0		5.61	9.18	14.79		0.04						4A4
767.1	769.6	2.5	1252	29.0		1.91	3.60	5.51		0.03						4A4
769.6	770.1	0.5	1253	98.0		5.17	6.94	12.11		0.15						4E1
779.2	779.8	0.6	1254	36.0		1.78	2.76	4.54		0.36						4E9
779.8	781.5	1.7	1255	155.0		11.86	7.87	19.73		0.12						4G4,3
781.5	783.0	1.5	1256	105.0		7.24	5.00	12.24		0.13						4G4,3
783.0	784.7	1.7	1257	145.0		8.05	9.44	17.49		0.20						4G4,3
784.7	785.7	1.0	1258	53.0		2.56	0.81	3.37		0.26						4K4,6
785.7	787.2	1.5	1259	99.0		7.36	8.45	15.81		0.12						4K4,6
787.2	789.2	2.0	1260	74.0		3.32	2.63	5.95		0.22						4K4,6
789.2	790.7	1.5	1261	100.0		7.26	8.79	16.05		0.17						4G4,3
790.7	792.3	1.6	1262	77.0		4.80	3.36	8.16		0.17						4E8,9,4
792.3	793.6	1.3	1263	33.0		1.20	1.11	2.31		0.48						4E8,9,4
793.6	795.0	1.4	1264	95.0		6.02	6.27	12.29		0.08						4G4,8,3

GEOCHEMICAL LOG

DY 79-X-11

Page 2 of 3

From	To	Int.	Samp. No.	Ag/AA GMS/MT	Ag/FA GMS/MT	Pb %	Zn %	Pb+Zn %	S.G.	Cu %	BaO %	Au GMS/MT	Po %	Py %	Hg %	Unit
795.0	796.2	1.2	1265	71.0		5.44	5.21	10.65		0.09						4G4,8,3
796.2	797.7	1.5	1266	35.0		3.23	2.16	5.39		0.19						4D8,9,4
797.7	799.7	2.0	1267	34.0		2.53	3.36	5.89		0.51						4D7,8,9,4
799.7	801.7	2.0	1268	28.0		1.77	3.48	3.48		0.22						4D7,8,9,4
801.7	802.9	1.2	1269	34.0		2.35	5.46	7.81		0.19						4D7,8,9,4
802.9	804.3	1.4	1270	13.0		0.63	0.77	1.40		0.39						4D7,8,9,4
804.3	805.2	0.9	1236	21.0		1.43	0.70	2.13		0.28						4A7,3,9
805.2	807.4	2.2	1237													4A7,3,9
807.4	808.9	1.5	1238	6.0		0.15	0.10			0.35						4L1,7,2,9
808.9	810.5	1.6	1239	9.0		0.20	0.36			0.47						4L1,7,2,9
810.5	812.2	1.7	1240	12.0		0.39	1.22			0.48						4L1,7,2,9
812.2	813.8	1.6	1241	9.0		0.15	0.19			0.22						4L1,7,2,9
819.1	819.8	0.7	1242	27.0		1.77	2.18	3.95		0.17						4E0
829.3	830.9	1.6	1271	4.0		0.06	0.06			0.06						4A0
830.9	832.0	1.1	1272	2.0		0.02	0.10			0.01						5D9
832.0	834.5	2.5	1273	6.0		0.32	0.21			0.09						4A0
834.5	835.0	0.5	1274	34.0		2.60	1.44	4.04		0.21						
835.0	836.9	1.9	1275	3.0		0.08	0.09			0.03						4L6,7,9
836.9	838.7	1.8	1276	4.0		0.05	0.06			0.05						4L6,7,9
873.3	875.2	1.9	1277	5.0		0.11	0.08			0.10						4L6,3,9
875.2	877.1	1.9	1278	7.0		0.32	0.02			0.03						
877.1	878.8	1.7	1279	6.0		0.30	0.14			0.16						4A0
878.8	880.2	1.4	1280	30.0		1.80	2.35	4.15		0.10						4A4,9
880.2	881.9	1.7	1281	23.0		1.59	4.15	5.74		0.02						
881.9	883.7	1.8	1282	29.0		2.16	4.17	6.33		0.03						
883.7	885.5	1.8	1283	49.0		3.35	6.41	9.76		0.05						
885.5	887.5	2.0	1284	3.0		0.09	0.19			0.15						5A9
887.5	889.4	1.9	1285	2.0		0.05	0.01			0.03						5A9
889.4	891.1	1.7	1286	3.0		0.18	0.08			0.02						5A9
891.1	892.5	1.4	1287	7.0		0.35	0.27			0.11						5A9
892.5	893.4	0.9	1288	28.0		1.77	2.04	3.81		0.27						4L7,4,1,9

79-X-12



Kamloops Research & Assay Laboratory Ltd.

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS

3

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS, B.C. V1S 1A7
TELEPHONE 372-2784 TELEX 048-8320

CERTIFICATE OF ASSAY

TO Cyprus Anvil Mining Corporation

Certificate No. K-2260

Date September 13, 1979.

I hereby certify that the following are the results of assays made by us upon the herein described DY core samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		Ounces Per Ton	g/tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent
22	X 1284		3	.09	.19	.15				
23	1285		2	.05	.01	.03				
24	1286		3	.18	.08	.02				
25	1287		7	.35	.27	.11				
26	1288		28	1.77	2.04	.27				
27	1289		25	1.84	2.12	.21				
28	1290		10	.67	.94	.21				
29	1291		7	.58	.84	.22				
30	1292		12	.91	1.37	.15				
31	1293		7	.38	.66	.08				
77-X-06 32	1315		4	.28	.36	.16				
33	1316		10	.55	2.56	.03				
34	1317		1	.06	.18	.02				
35	1318		9	.57	2.66	.06				
36	1319		Tr	.12	.43	.01				
37	1320		7	.32	.31	.05				
38	1321		6	.14	.09	.08				
39	1322		18	.44	.27	.37				
40	1323		11	.08	.03	.38				
79-X-12 41	X 1324		45	4.16	4.36	.20				

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.

Tr denotes "trace"

DAS for P.S.B.
Registered Assayer, Province of British Columbia



Kamloops Research & Assay Laboratory Ltd.

2095 WEST TRANS CANADA HIGHWAY—KAMLOOPS, B.C. V1S 1A7
TELEPHONE 372-2784 - TELEX 048-8320

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS

CERTIFICATE OF ASSAY

TO Cyprus Anvil Mining Corporation

Certificate No. K-2238

Date August 29, 1979.

Vangorda
drill core

I hereby certify that the following are the results of assays made by us upon the herein described drill core samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		Ounces Per Ton	g/tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent
21	V 1125		56	3.88	5.57	.24				
22	1126		52	3.86	4.61	.17				
23	1127		13	1.41	1.15	.07				
24	1128		81	6.85	6.75	.15				
25	1129		77	6.07	7.16	.13				
26	1130		73	5.38	5.90	.14				
V-30 27	1131		22	.70	.72	.26				
28	1132		23	.28	.94	.43				
29	1133		28	.97	.80	.26				
30	1134		46	2.08	2.16	.29				
V-312 31	1199		23	2.20	2.90	.09				
32	1200		8	.24	.38	.11				
33	1201		40	3.08	3.70	.17				
34	1202		56	4.77	6.78	.05				
35	1203		69	5.00	5.66	.17				
DY-12 36	1204		48	3.48	3.84	.17				
37	1205		63	5.14	3.87	.10				
38	1206		79	5.56	6.28	.09				
39	1207		82	5.79	5.98	.05				
40	V 1208		76	5.74	5.27	.11				

NOTE:

Rejects retained three weeks
Pulps retained three months
unless otherwise arranged.

.....*R.A. Blundell*.....
Registered Assayer, Province of British Columbia



Kamloops Research & Assay Laboratory Ltd.

2095 WEST TRANS CANADA HIGHWAY--KAMLOOPS, B.C. V1S 1A7
TELEPHONE 372-2784 - TELEX 048-8320

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS

CERTIFICATE OF ASSAY

TO Cyprus Anvil Mining Corporation

Certificate No. K-2238

Date August 29, 1979.

I hereby certify that the following are the results of assays made by us upon the herein described Vangorda drill core samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		Ounces Per Ton	g/tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent
	Repeats:									
	V 1106 312		12	.21	.64	.14				
	1112 313		10	.26	.59	.12				
	1209 X12		41	1.90	1.37	.29				
	V 1224 X7		20	.84	.90	.10				
	Standards:									
	MP1		58	1.79	15.96	-				
	RU1		-	-	2.29	-				
	Tails		-	.49	.92	.13				
	100		95	5.47	9.00	.11				
	200		82	4.89	6.48	.16				
	300		40	2.33	4.35	.04				

NOTE:

Rejects retained three weeks
Pulps retained three months
unless otherwise arranged.

c.c. Mr. Darryl Hanson

.....
R. Blundell
Registered Assayer, Province of British Columbia



Kamloops Research & Assay Laboratory Ltd.

2095 WEST TRANS CANADA HIGHWAY-KAMLOOPS, B.C. V1S 1A7
TELEPHONE 372-2784 - TELEX 048-8320

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS

CERTIFICATE OF ASSAY

TO Cyprus Anvil Mining Corporation

Certificate No. K-2244

Date September 6, 1979.

BY

I hereby certify that the following are the results of assays made by us upon the herein described drill core samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		Ounces Per Ton	g/tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent
42	X 1135		109	6.30	8.30	.27				
43	1136		16	1.01	.67	.39				
44	1137		15	1.41	.95	.24				
45	1138		34	6.50	.93	.26				
46	1139		100	7.78	6.44	.10				
47	1140		52	3.73	2.97	.16				
48	1141		95	7.07	5.80	.08				
49	1142		74	6.86	3.12	.29				
50	1143		97	6.12	6.66	.11				
51	1144		25	1.37	.99	.32				
52	1145		14	.34	.29	.35				
53	1146		18	1.15	.83	.42				
54	1147		315	12.35	6.50	.06				
55	1148		31	2.60	4.47	.04				
56	1149		79	7.00	5.84	.10				
57	1150		84	5.40	5.80	.06				
58	1227		8	.42	.23	.25				
59	1228		32	2.74	1.79	.48				
60	X 1129		5	.73	.51	.05				

DY
79-X-11

DY
79-X-12

NOTE:
Rejects retained three weeks
Pulps retained three months
unless otherwise arranged.

R. B. Blundell
Registered Assayer, Province of British Columbia



Kamloops Research & Assay Laboratory Ltd.

2095 WEST TRANS CANADA HIGHWAY--KAMLOOPS, B.C. V1S 1A7
TELEPHONE 372-2784 - TELEX 048-8320

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS

CERTIFICATE OF ASSAY

TO Cyprus Anvil Mining Corporation

K-2244

Certificate No. _____

Date September 6, 1979.

I hereby certify that the following are the results of assays made by us upon the herein described DY drill core samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		Ounces Per Ton	g/tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent
61	X 1230		1	.18	.14	.04				
62	1231		28	1.69	1.70	.35				
63	1232		22	1.00	1.03	.36				
64	1233		9	.63	1.07	.08				
65	1234		8	.63	.75	.08				
66	1235		Tr	.03	.04	.07				
67	1236		21	1.43	.70	.28				
68	1237		5	.22	.15	.43				
69	1238		6	.15	.10	.35				
70	1239		9	.20	.36	.47				
71	1240		12	.39	1.22	.48				
72	1241		9	.15	.19	.22				
73	1242		27	1.77	2.18	.17				
74	1270		13	.63	.77	.39				
75	1271		4	.06	.06	.06				
76	1272		2	.02	.10	.01				
77	1273		6	.32	.21	.09				
78	1274		34	2.60	1.44	.21				
79	1275		3	.08	.09	.03				
80	X 1276		4	.05	.06	.05				

NOTE:

Rejects retained three weeks
Pulps retained three months
unless otherwise arranged.

.....*B. A. Shindell*.....
Registered Assayer, Province of British Columbia

CYPRUS ANVIL MINING CORPORATION

DY 79-X-12

GEOCHEMICAL LOG

Kamloops Research and Assay Lab.

<u>From</u>	<u>To</u>	<u>Int.</u>	<u>Samp. No.</u>	<u>Ag/AA GMS/MT</u>	<u>Ag/FA GMS/MT</u>	<u>Pb %</u>	<u>Zn %</u>	<u>Pb+Zn %</u>	<u>S.G.</u>	<u>Cu %</u>	<u>BaO %</u>	<u>Au GMS/MT</u>	<u>Po %</u>	<u>Py %</u>	<u>Hg %</u>	<u>Unit</u>
723.8	724.4	0.6	1201	40.0		3.08	3.70	6.78		0.17						4E1
724.4	725.0	0.6	1202	56.0		4.77	6.78	11.55		0.05						4G4
725.0	727.0	2.0	1203	69.0		5.00	5.66	10.66		0.17						4D4/4G4,8
727.0	729.0	2.0	1204	48.0		3.48	3.84	7.32		0.17						4G4,8
729.0	730.0	1.0	1205	63.0		5.14	3.87	9.01		0.10						4G4,0
730.0	732.3	2.3	1206	79.0		5.56	6.28	11.84		0.09						4G4,8
732.3	733.5	1.2	1207	82.0		5.79	5.98	11.77		0.05						4G4,8
733.5	735.0	1.5	1208	76.0		5.74	5.27	11.01		0.11						4D0/4G4
735.0	736.1	1.1	1209	40.0		2.10	1.50	3.60		0.24						4E8,7,9
736.1	737.3	1.2	1210	41.0		3.45	4.12	7.57		0.05						4G4,1
737.3	737.7	0.4	1211	56.0		4.09	4.04	8.13		0.08						4E4
737.7	738.8	1.1	1212	24.0		1.53	0.99	2.52		0.18						4K1
738.8	740.8	2.0	1213	22.0		1.49	1.93	3.42		0.15						4C0
740.8	743.1	2.3	1214	20.0		1.31	1.31	2.62		0.17						4C0
743.1	745.1	2.0	1215	19.0		0.88	0.89	1.77		0.35						4C7,9
745.1	746.0	0.9	1216	8.0		0.11	0.08	0.19		0.38						4C7,9
746.0	747.0	1.0	1217	6.0		0.11	0.08	0.19		0.38						4C8
747.0	749.5	2.5	1218	8.0		0.44	0.66	1.10		0.11						4A9
749.5	750.0	0.5	1219	39.0		2.63	1.66	4.29		0.23						4E0
750.0	750.8	0.8	1220	91.0		5.54	8.88	14.42		0.29						4G0
750.8	751.4	0.6	1221	35.0		1.64	2.97	4.61		0.08						4A0
751.4	753.4	2.0	1222	28.0		0.92	0.67	1.59		0.41						4E8
753.4	754.9	1.5	1223	21.0		0.33	0.10	0.43		0.42						4E8
763.6	764.1	0.5	1224	22.0		0.85	0.91	1.76		0.10						4A0
764.1	764.5	0.4	1225	30.0		1.06	1.10	2.16		0.24						4E0
764.5	765.5	1.0	1226	24.0		0.74	0.73	1.47		0.33						4G4
765.5	766.2	0.7	1227	8.0		0.42	0.23	0.65		0.25						4A0
766.2	767.2	1.0	1228	32.0		2.74	1.79	4.53		0.48						4G4,8
767.2	769.3	2.1	1229	5.0		0.73	0.51	1.24		0.05						4L4/4A0
769.3	771.8	2.5	1230	1.0		0.18	0.14	0.32		0.04						4L7

79-X-13



Kamloops Research & Assay Laboratory Ltd.

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS, B.C. V1S 1A7
TELEPHONE 372-2784 TELEX 048-8320

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS

3

CERTIFICATE OF ASSAY

TO Cyprus Anvil Mining Corporation,

Certificate No. K-2291

Date September 27, 1979.

I hereby certify that the following are the results of assays made by us upon the herein described DY drill core samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		Ounces Per Ton	g/tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent
25	X 1488		56	3.42	1.48	.13				
26	1489		77	7.60	4.24	.18				
27	1490		59	3.38	4.93	.13				
28	1491		87	7.48	9.36	.05				
29	1492		107	6.38	8.33	.02				
30	1493		62	4.01	5.04	.03				
31	1494		110	7.46	9.05	.03				
32	1495		93	7.66	8.63	.04				
33	1496		120	7.31	9.07	.03				
34	X 1497		98	9.24	6.02	.04				
Standards -- Page 2										

DY 13

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.

Jas for P&S

Registered Assayer, Province of British Columbia



Kamloops Research & Assay Laboratory Ltd.

B.C. LICENSED AYERS
GEOCHEMICAL ANALYSTS

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS, B.C. V1S 1A7
TELEPHONE 372-2784 TELEX 048-8320

CERTIFICATE OF ASSAY

TO Cyprus Anvil Mining Corporation

Certificate No. K-2291

Date September 27, 1979.

I hereby certify that the following are the results of assays made by us upon the herein described Vangorda
drill core samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		Ounces Per Ton	g/tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent
21	V 1484		50	3.60	4.12	.06				
22	1485		65	3.14	3.24	.06				
23	1486		110	6.01	8.62	.30				
24	V 1487		18	.95	1.34	.14				
	Repeats:									
	V 1464		19	1.09	2.12	.06				
	V 1482		99	6.58	12.08	.22				
	Standards:									
	MP-1		58	1.78	15.7	-				
	RU-1		7	-	2.10	-				
	Tails		-	.49	.92	.12				
	100		95	5.44	8.94	.10				
	200		82	4.98	6.79	.15				
	300		40	2.18	4.35	.04				

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.

JAS fa *ORS*
Registered Assayer, Province of British Columbia

79-X-14



Kamloops Research & Assay Laboratory Ltd.

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS, B.C. V1S 1A7
TELEPHONE 372-2784 TELEX 048-8320

CERTIFICATE OF ASSAY

TO Cyprus Anvil Mining Corporation,

330 - 355 Burrard St.,

Vancouver, B. C. V6C 2G8 Attention: Dr. G. Simpson

Certificate No. K-2352

Date October 19, 1979.

I hereby certify that the following are the results of assays made by us upon the herein described DY core samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		Ounces Per Ton	g/tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent
1	X 3066		49	3.70	2.76	.26				
2	3067		8	.18	.14	.62				
X-14 3	3068		22	1.52	.77	.49				
4	3069		Tr	.02	Tr	Tr				
5	3070		20	1.68	.87	.29				
6	3071		2	.47	.35	.07				
7	3072		51	3.81	2.98	.24				
8	3073		47	3.26	2.92	.15				
9	3074		42	3.43	2.91	.17				
10	3075		15	.79	.67	.23				
11	3076		3	.19	.11	.04				
12	3077		23	1.24	1.18	.16				
13	3078		42	3.54	2.84	.25				
14	3079		56	3.86	3.35	.28				
15	3080		79	5.53	6.08	.13				
16	3081		58	2.20	1.97	.11				
17	3082		25	1.43	2.13	.10				
18	3083		23	1.50	2.96	.10				
19	3084		6	.19	.53	.45				
20	X 3085		5	.73	.20	.19				

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.


Registered Assayer, Province of British Columbia



Kamloops Research & Assay Laboratory Ltd.

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS, B.C. V1S 1A7
TELEPHONE 372-2784 TELEX 048-8320

CERTIFICATE OF ASSAY

TO Cyprus Anvil Mining Corporation

Certificate No. K-2352

Date October 19, 1979.

I hereby certify that the following are the results of assays made by us upon the herein described DY core samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		Ounces Per Ton	g/tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent
21	X 3086		8	.51	2.07	.52				
22	3087		3	.07	.08	.21				
23	3088		15	.10	.20	.28				
24	3089		34	1.95	2.92	.36				
25	3090		22	.80	1.01	.34				
26	3091		85	7.10	7.87	.08				
27	3092		22	.59	.71	.31				
28	3093		49	3.07	5.40	.12				
29	3094		70	5.68	7.93	.06				
30	3095		60	4.17	4.90	.14				
31	3096		73	5.26	4.90	.09				
32	3097		51	2.95	4.87	.28				
33	3098		68	4.95	1.58	.22				
34	3099		115	8.37	5.84	.09				
35	3100		83	6.94	6.08	.18				
36	3133		88	7.20	3.70	.22				
37	3134		33	2.14	2.10	.27				
38	3135		41	3.51	1.69	.22				
39	3136		97	7.82	9.18	.08				
40	X 3137		57	5.04	6.33	.08				

X-14

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.

DAB for PAB
Registered Assayer, Province of British Columbia



Kamloops Research & Assay Laboratory Ltd.

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS, B.C. V1S 1A7
TELEPHONE 372-2784 TELEX 048-8320

CERTIFICATE OF ASSAY

TO Cyprus Anvil Mining Corporation

Certificate No. K-2352

Date October 19, 1979.

I hereby certify that the following are the results of assays made by us upon the herein described DY core samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		Ounces Per Ton	g/tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent
41	X 3138		43	2.78	2.74	.20				
42	3139		19	.55	.52	.35				
43	3140		87	7.62	9.96	.05				
44	3141		5	.07	.06	L .01				
45	3142		92	8.82	9.98	.05				
46	3143		27	2.09	2.11	.24				
47	3144		8	.42	.71	.08				
48	3145		13	.25	.41	.29				
49	3146		24	1.01	1.79	.20				
50	3147		47	2.88	3.59	.12				
51	3148		91	5.92	11.19	.09				
52	3149		50	2.84	4.37	.05				
53	3150		6	.23	.64	.07				
54	3151		23	1.23	.67	.22				
55	3152		47	3.55	3.02	.19				
56	3153		6	.16	.14	.11				
57	3154		36	2.57	2.05	.13				
58	3155		7	.08	.02	.11				
59	3156		23	1.10	1.33	.22				
60	X 3157		1	.13	.18	.12				

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.


Registered Assayer, Province of British Columbia



Kamloops Research & Assay Laboratory Ltd.

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS, B.C. V1S 1A7
TELEPHONE 372-2784 TELEX 048-8320

CERTIFICATE OF ASSAY

TO Cyprus Anvil Mining Corporation

Certificate No. K-2352

Date October 19, 1979.

I hereby certify that the following are the results of assays made by us upon the herein described DY core samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		Ounces Per Ton	g/tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent
61	X 3158		1	.07	.07	.08				
62	3159		10	.70	.38	.13				
X-14 63	3160		16	1.19	3.19	.12				
64	3161		37	2.68	2.98	.19				
65	3162		Tr	.20	.48	.03				
66	3163		2	.31	.39	.12				
67	3164		17	1.03	.74	.37				
X-15 68	3165		6	.18	.09	.19				
69	3166		68	4.69	3.46	.11				
70	3167		41	2.75	2.34	.20				
71	3168		3	.18	.11	.02				
72	3169		31	2.30	2.58	.16				
73	3170		34	2.68	3.06	.22				
74	3171		33	2.26	2.44	.29				
75	3172		6	.33	.66	.12				
76	3173		41	4.01	3.92	.22				
77	3174		12	.84	.65	.15				
78	3175		Tr	.06	.21	Tr				
79	3176		Tr	.10	.06	.02				
80	X 3177		38	2.39	5.69	.05				

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.

WAS for PLS
Registered Assayer, Province of British Columbia



Kamloops Research & Assay Laboratory Ltd.

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS, B.C. V1S 1A7
TELEPHONE 372-2784 TELEX 048-8320

CERTIFICATE OF ASSAY

TO Cyprus Anvil Mining Corporation

Certificate No. K-2352

Date October 19, 1979.

I hereby certify that the following are the results of assays made by us upon the herein described DY core samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		Ounces Per Ton	g/tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent
81	X 3178		18	.67	.95	.04				
82	3179		13	.34	.25	.01				
X-15 83	3180		2	.01	Tr	Tr				
84	3181		1	.07	.02	.11				
85	3182		2	.09	.07	.08				
86	X 3183		2	.13	.09	.06				
	Repeats:									
	X 3100		86	6.90	6.02	.18				
X-14	3139		21	.55	.52	.35				
	3075		16	.79	.67	.23				
	3072		53	3.77	3.02	.25				
	X 3170 -15		35	2.68	3.13	.23				

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.

QAS for Pess
Registered Assayer, Province of British Columbia

GEOCHEMICAL LOG

Kamloops Research and Assay Lab.

From	To	Int.	Sample No.	Ag/AA GMS/MT	Ag/FA GMS/MT	Pb %	Zn %	Pb+Zn %	S.G.	Cu %	BaO %	Au GMS/MT	Po %	Py %	Unit
686.3	688.6	2.3	3066	49.0		3.70	2.76	6.46		0.26					4C8
688.6	689.0	0.4	3067	8.0		0.18	0.14	0.32		0.62					4L0
689.0	689.8	0.8	3068	22.0		1.52	0.77	2.29		0.49					4C2,8
689.8	690.6	0.8	3069	TR		0.02	TR			TR					4L0
704.1	705.7	1.6	3070	20.0		1.68	0.87	2.55		0.29					4C7
705.7	706.4	0.7	3071	2.0		0.47	0.35	0.82		0.07					4A0/4L7,2
706.4	708.4	2.0	3072	51.0		3.81	2.98	6.79		0.24					4G8
708.4	710.4	2.0	3073	47.0		3.26	2.92	6.18		0.15					4G8
710.4	712.5	2.1	3074	42.0		3.43	2.91	6.34		0.17					4G8/4C8
712.5	713.0	0.5	3075	15.0		0.79	0.67	1.46		0.23					4L7,2
713.0	714.3	1.3	3076	3.0		0.19	0.11	0.30		0.04					4A0
714.3	715.5	1.2	3077	23.0		1.24	1.18	2.42		0.16					4L2,7
715.5	717.5	2.0	3078	42.0		3.54	2.84	6.38		0.25					4G8
717.5	719.5	2.0	3079	56.0		3.86	3.35	7.21		0.28					4G8
719.5	720.5	1.0	3080	79.0		5.53	6.08	11.61		0.13					4G8
720.5	720.8	0.3	3081	58.0		2.20	1.97	4.17		0.11					4E/4C
720.8	722.2	1.4	3082	25.0		1.43	2.13	3.56		0.10					4A0
722.2	723.9	1.7	3083	23.0		1.50	2.96	4.46		0.10					4A0
734.1	734.9	0.8	3084	6.0		0.19	0.53			0.45					4C2
742.0	743.9	1.9	3085	5.0		0.73	0.20			0.19					4L4,2/4L2
743.9	745.9	2.0	3086	8.0		0.51	2.07	2.58		0.52					4L6,2,7
745.9	747.9	2.0	3087	3.0		0.07	0.08			0.21					4L6,2,7
747.9	749.9	2.0	3088	15.0		0.10	0.20			0.28					4L6,2,7
787.7	788.3	0.6	3089	34.0		1.95	2.92	4.87		0.36					4C0
788.3	788.8	0.5	3090	22.0		0.80	1.01	1.81		0.34					4E0
788.8	789.1	0.3	3091	85.0		7.10	7.87	14.97		0.08					4G4
789.1	790.3	1.2	3092	22.0		0.59	0.71	1.30		0.31					4E0
790.3	791.6	1.3	3093	49.0		3.07	5.40	8.47		0.12					4D4,6
791.6	792.1	0.5	3094	70.0		5.68	7.93	13.61		0.06					4G0
792.1	792.7	0.6	3095	60.0		4.17	4.90	9.07		0.14					4D6
792.7	794.2	1.5	3096	73.0		5.26	4.90	10.16		0.09					4E4

<u>From</u>	<u>To</u>	<u>Int.</u>	<u>Sample No.</u>	<u>Ag/AA GMS/MT</u>	<u>Ag/FA GMS/MT</u>	<u>Pb %</u>	<u>Zn %</u>	<u>Pb+Zn %</u>	<u>S.G.</u>	<u>Cu %</u>	<u>BaO %</u>	<u>Au GMS/MT</u>	<u>Po %</u>	<u>Py %</u>	<u>Unit</u>
794.2	794.5	0.3	3097	51.0		2.95	4.87	7.82		0.28					4G0
794.5	795.7	1.2	3098	68.0		4.95	1.58	6.53		0.22					4E4
795.7	796.1	0.4	3099	115.0		8.37	5.84	14.21		0.09					4H2
796.1	798.1	2.0	3100	83.0		6.94	6.08	13.02		0.18					4K4,1
798.1	800.1	2.0	3133	88.0		7.20	3.70	10.90		0.22					4K4,1
800.1	802.1	2.0	3134	33.0		2.14	2.10	4.24		0.27					4K4,1
802.1	804.1	2.0	3135	41.0		3.51	1.69	5.20		0.22					4K4,1
804.1	804.6	0.5	3136	97.0		7.82	9.18	17.00		0.08					4K4,1
804.6	805.1	0.5	3137	57.0		5.04	6.33	11.37		0.08					4G4
805.1	807.1	2.0	3138	43.0		2.78	2.74	5.52		0.20					4K4,1
807.1	808.7	1.6	3139	19.0		0.55	0.52	1.07		0.35					4K4,1
808.7	809.1	0.4	3140	87.0		7.62	9.96	17.58		0.05					4G4
809.1	811.5	2.4	3141	5.0		0.07	0.06	0.13		0.01					5D3
811.5	812.4	0.9	3142	92.0		8.82	9.98	18.80		0.05					4G4
812.4	814.3	1.9	3143	27.0		2.09	2.11	4.20		0.24					4E4,1
814.3	815.6	1.3	3144	8.0		0.42	0.71	1.13		0.08					4A0
815.6	817.6	2.0	3145	13.0		0.25	0.41	0.66		0.29					4C0
817.6	819.3	1.7	3146	24.0		1.01	1.79	2.80		0.20					4C0
819.3	821.8	2.5	3147	47.0		2.88	3.59	6.47		0.12					4A0
821.8	822.5	0.7	3148	91.0		5.92	11.19	17.11		0.09					4G4
822.5	824.8	2.3	3149	50.0		2.84	4.37	7.21		0.05					4A0
854.5	856.3	1.8	3150	6.0		0.23	0.64	0.87		0.07					4L4
856.3	856.8	0.5	3151	23.0		1.23	0.67	1.90		0.22					4E0
856.8	857.7	0.9	3152	47.0		3.55	3.02	6.57		0.19					4E7,8,4
902.4	903.9	1.5	3153	6.0		0.16	0.14	0.30		0.11					4A0
903.9	904.2	0.3	3154	36.0		2.57	2.05	4.62		0.13					4A7,9
904.2	905.0	0.8	3155	7.0		0.08	0.02	0.10		0.11					4C7
905.0	905.6	0.6	3156	23.0		1.10	1.33	2.43		0.22					4A7
905.6	907.6	2.0	3157	1.0		0.13	0.18			0.12					4A0
907.6	908.9	1.3	3158	1.0		0.07	0.07			0.08					4A0
913.4	915.4	2.0	3159	10.0		0.70	0.38			0.13					4A0
915.4	916.6	1.2	3160	16.0		1.19	3.19	4.38		0.12					4A0
927.9	929.0	1.1	3161	37.0		2.68	2.98	5.66		0.19					4H4,9
929.0	929.7	0.7	3162	TR		0.20	0.48			0.03					4L1,7

79-X-14

BEST SECTIONS:

		<u>Int.</u>	<u>Ag</u> <u>GMS/MT</u>	<u>Pb %</u>	<u>Zn %</u>	<u>Pb+Zn</u> <u>%</u>
715.5	720.5	5.0	55.0	4.06	3.69	7.75
and						
790.3	805.1	14.8	64.5	4.96	4.18	9.14
(including)						
790.3	800.1	9.8	74.4	5.68	4.75	10.43
(including)						
795.7	800.1	4.4	88.2	7.19	4.98	12.17
and						
821.8	824.8	3.0	59.5	3.56	5.96	9.52

79-X-15



Kamloops Research & Assay Laboratory Ltd.

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS, B.C. V1S 1A7
TELEPHONE 372-2784 TELEEX 048-8320

CERTIFICATE OF ASSAY

TO Cyprus Anvil Mining Corporation

Certificate No. K-2352

Date October 19, 1979.

I hereby certify that the following are the results of assays made by us upon the herein described DY core samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		Ounces Per Ton	g/tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent
61	X 3158		1	.07	.07	.08				
62	3159		10	.70	.38	.13				
X-14 63	3160		16	1.19	3.19	.12				
64	3161		37	2.68	2.98	.19				
65	3162		Tr	.20	.48	.03				
66	3163		2	.31	.39	.12				
67	3164		17	1.03	.74	.37				
X-15 68	3165		6	.18	.09	.19				
69	3166		68	4.69	3.46	.11				
70	3167		41	2.75	2.34	.20				
71	3168		3	.18	.11	.02				
72	3169		31	2.30	2.58	.16				
73	3170		34	2.68	3.06	.22				
74	3171		33	2.26	2.44	.29				
75	3172		6	.33	.66	.12				
76	3173		41	4.01	3.92	.22				
77	3174		12	.84	.65	.15				
78	3175		Tr	.06	.21	Tr				
79	3176		Tr	.10	.06	.02				
80	X 3177		38	2.39	5.69	.05				

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.

DAB for PGB
Registered Assayer, Province of British Columbia



Kamloops Research & Assay Laboratory Ltd.

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS, B.C. V1S 1A7
TELEPHONE 372-2784 TELEX 048-8320

CERTIFICATE OF ASSAY

TO Cyprus Anvil Mining Corporation

Certificate No. K-2352

Date October 19, 1979.

I hereby certify that the following are the results of assays made by us upon the herein described DY core samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		Ounces Per Ton	g/tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent
81	X 3178		18	.67	.95	.04				
82	3179		13	.34	.25	.01				
83	3180		2	.01	Tr	Tr				
84	3181		1	.07	.02	.11				
85	3182		2	.09	.07	.08				
86	X 3183		2	.13	.09	.06				
	Repeats:									
	X 3100		86	6.90	6.02	.18				
	3139		21	.55	.52	.35				
	3075		16	.79	.67	.23				
	3072		53	3.77	3.02	.25				
X-15	X 3170 -15		35	2.68	3.13	.23				

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.

QAS for PAB
Registered Assayer, Province of British Columbia

GEOCHEMICAL LOG

Kamloops Research and Assay Lab.

<u>From</u>	<u>To</u>	<u>Int.</u>	<u>Sample No.</u>	<u>Ag/AA GMS/MT</u>	<u>Ag/FA GMS/MT</u>	<u>Pb %</u>	<u>Zn %</u>	<u>Pb+Zn %</u>	<u>S.G.</u>	<u>Cu %</u>	<u>BaO %</u>	<u>Au GMS/MT</u>	<u>Po %</u>	<u>Py %</u>	<u>Unit</u>
476.3	477.0	0.7	3163	2.0		0.31	0.39	0.70		0.12					4L7
477.0	479.0	2.0	3164	17.0		1.03	0.74	1.77		0.37					4K8
479.0	480.7	1.7	3165	6.0		0.18	0.09	0.27		0.19					4K8
480.7	481.6	0.9	3166	68.0		4.69	3.49	8.18		0.11					4G/E
481.6	482.7	1.1	3167	41.0		2.75	2.34	5.09		0.20					4K0
482.7	483.7	1.0	3168	3.0		0.18	0.11	0.29		0.02					4K0/5D6
483.7	484.8	1.1	3169	31.0		2.30	2.58	4.88		0.16					4C0
484.8	486.8	2.0	3170	34.0		2.68	3.06	5.74		0.22					4C8
486.8	488.9	2.1	3171	33.0		2.26	2.44	4.70		0.29					4C8
488.9	489.8	0.9	3172	6.0		0.33	0.66	0.99		0.12					4L7,2
489.8	490.2	0.4	3173	41.0		4.01	3.92	7.93		0.22					4C8
490.2	492.2	2.0	3174	12.0		0.84	0.65	1.49		0.15					4L7,5
492.2	494.2	2.0	3175	TR		0.06	0.21	0.27		TR					4L7,5
494.2	496.4	2.2	3176	TR		0.10	0.06	0.16		0.02					4L7,5
514.9	516.9	2.0	3177	38.0		2.39	5.69	8.08		0.05					4A0
516.9	518.3	1.4	3178	18.0		0.67	0.95	1.62		0.04					4A0
518.3	519.8	1.5	3179	13.0		0.34	0.25			0.01					4C0
519.8	521.9	2.1	3180	2.0		0.01	TR			TR					4A0
529.4	531.4	2.0	3181	1.0		0.07	0.02			0.11					4A0
531.4	533.4	2.0	3182	2.0		0.09	0.07			0.08					4A0
533.4	534.6	1.2	3183	2.0		0.13	0.09			0.06					4A0

BEST SECTION:

480.7	488.9	8.2		34.2		2.44	2.43	4.87							
-------	-------	-----	--	------	--	------	------	------	--	--	--	--	--	--	--

79-X-16



Kamloops Research & Assay Laboratory Ltd.

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS, B.C. V1S 1A7
TELEPHONE 372-2784 TELEEX 048-8320

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS

CERTIFICATE OF ASSAY

TO Cyprus Anvil Mining Corporation

Certificate No. K-2377

Date October 29, 1979.

I hereby certify that the following are the results of assays made by us upon the herein described

Vangorda
drill core samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		Ounces Per Ton	g/tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent
41	V 3259		98	7.01	9.79	.21				
42	3260		96	6.97	7.36	.20				
43	3261		77	5.38	7.36	.10				
44	3262		30	2.22	1.59	.34				
45	3263		26	1.54	2.05	.12				
46	3264		37	3.17	2.08	.16				
47	3265		45	3.00	2.90	.16				
48	3266		34	1.95	2.07	.16				
49	3267		28	3.72	2.00	.21				
V-321 50	3268		54	4.91	4.43	.21				
51	3269		34	1.97	1.80	.13				
52	3270		65	3.83	4.72	.23				
53	3271		40	3.04	3.95	.23				
54	3272		47	3.93	5.19	.17				
55	3273		18	.71	.87	.21				
56	3274		14	.16	.09	.31				
57	3275		14	.61	.82	.15				
58	3276		7	.30	.78	.14				
59	3277		18	1.16	.65	.11				
X-16 60	V 3278		36	2.56	1.75	.23				

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.

DAB for PSB
Registered Assayer, Province of British Columbia



Kamloops Research & Assay Laboratory Ltd.

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS, B.C. V1S 1A7
 TELEPHONE 372-2784 TELEX 048-8320

B.C. LICENSED ASSAYERS
 GEOCHEMICAL ANALYSTS

CERTIFICATE OF ASSAY

TO Cyprus Anvil Mining Corporation

Certificate No. K-2377

Date October 29, 1979.

I hereby certify that the following are the results of assays made by us upon the herein described

Vangorda
drill core samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		g/tonne	g/tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent
X-16 61	V 3279		24	1.74	2.22	.10				
62	3280		35	1.78	.38	.30				
63	3291		1	.04	.03	.03				
64	3294		51	2.98	3.57	.05				
65	3295		13	.81	1.32	.31				
v-47-R 66	3296		10	.43	.93	.19				
67	3297 X	Tr	-	-	-	.06				
68	3301		47	3.24	3.82	.05				
69	3302		64	4.62	5.40	.06				
70	3303		69	4.38	6.14	.07				
71	3304		82	5.04	6.77	.13				
v 47-R 72	3305		54	3.98	4.04	.16				
73	3306		54	3.16	5.21	.12				
74	3307		130	9.93	8.18	.05				
75	3308		18	.98	1.04	.05				
76	3309		92	5.16	6.61	.09				
77	3310		58	3.30	3.93	.03				
78	3311		52	2.96	3.78	.04				
79	3312		61	3.66	7.22	.04				
80	3313		55	2.88	6.44	.02				

NOTE:
 Rejects retained three weeks.
 Pulp retained three months
 unless otherwise arranged.

D.A.S. for P.A.S.
 Registered Assayer, Province of British Columbia



Kamloops Research & Assay Laboratory Ltd.

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS, B.C. V1S 1A7
TELEPHONE 372-2784 TELEX 048-8320

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS

CERTIFICATE OF ASSAY

TO Cyprus Anvil Mining Corporation

Certificate No. K-2377

Date October 29, 1979.

I hereby certify that the following are the results of assays made by us upon the herein described DY core samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		Ounces Per Ton	g/tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent
X-13	113	DY 3128	74	2.79	3.61	.20				
	114	3129	1	.04	.06	.06				
	115	3130	1	.06	.24	.10				
	116	3131	17	1.32	1.01	.12				
	117	3132	49	3.96	4.04	.16				
	118	3281	10	.51	.34	.07				
	119	3282	26	1.57	1.63	.27				
X-16	120	3283	23	1.36	.69	.38				
	121	3284	25	1.71	1.48	.35				
	122	3285	18	1.33	.83	.16				
	123	3286	9	.74	.54	.09				
	124	3287	26	1.54	1.13	.24				
	125	3288	67	5.10	4.64	.27				
	126	3289	2	.03	.04	.02				
	127	3290	2	.02	.02	.02				
	128	3292	1	.08	.04	.08				
V-47-R	129	3293	50	3.30	9.01	.13				
	130	3368	1	.07	.06	.05				
X-18	131	3369	15	1.43	4.56	.14				
	132	DY 3370	Tr	.09	.21	.02				

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.

DAB for PAB
Registered Assayer, Province of British Columbia



Kamloops Research & Assay Laboratory Ltd.

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS, B.C. V1S 1A7
TELEPHONE 372-2784 TELEX 048-8320

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS

CERTIFICATE OF ASSAY

TO Cyprus Anvil Mining Corporation

Certificate No. K-2377

Date October 29, 1979.

I hereby certify that the following are the results of assays made by us upon the herein described Blind Creek samples

Kral No.	Marked	GOLD	SILVER	Pb	Zn	Cu				
		Ounces Per Ton	g/tonne	Percent	Percent	Percent	Percent	Percent	Percent	Percent
BC-04 172 173 174	BC 3365 BC 3366 BC 3367		Tr	Tr	.02	.01				
			Tr	.05	.04	.05				
			Tr	Tr	.02	.03				
	Repeats:									
	DY 3130 X-13		1	.07	.24	.11				
X-16	3281 X-16		9	.51	.34	.07				
	3131 X-13		20	1.33	1.04	.13				
X-16	DY 3399 X-16		77	4.45	5.24	.23				
	Standards:									
	MP-1		58	1.90	16.14	2.07				
	KC-1		1094	6.79	19.96	.11				
	RU-1		-	-	2.24	.859				
	100		93	5.41	8.97	.106				
	200		82	5.03	6.71	.155				
	300		40	2.40	4.22	.03				

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.

c.c. Mr. Darryl Hanson

DAS for Pys
Registered Assayer, Province of British Columbia

GEOCHEMICAL LOG

Kamloops Research and Assay Lab.

From	To	Int.	Samp. No.	Ag/AA GMS/MT	Ag/FA GMS/MT	Pb %	Zn %	Pb+Zn %	S.G.	Cu %	BaO %	Au GMS/MT	Po %	Py %	Hg %	Unit
641.5	642.0	0.5	3277	18.0		1.16	0.65	1.81		0.11						4L2,7,4
642.0	642.5	0.5	3278	36.0		2.56	1.75	4.31		0.23						4C8
642.5	644.1	1.6	3279	24.0		1.74	2.22	3.96		0.10						4A4,7
644.1	645.1	1.0	3280	35.0		1.78	0.38	2.16		0.30						4E1
645.1	647.9	2.8	3281	10.0		0.51	0.34	0.85		0.07						4L3,7
647.9	649.1	1.2	3282	26.0		1.57	1.63	3.20		0.27						4L2,7,4
649.1	651.1	2.0	3283	23.0		1.36	0.69	2.05		0.38						4C2,7,4,8
651.1	652.1	1.0	3284	25.0		1.71	1.48	3.19		0.35						4C2,7,4,8
652.1	655.0	2.9	3285	18.0		1.33	0.83	2.16		0.16						4L4,8,2
655.0	656.8	1.8	3286	9.0		0.74	0.54	1.28		0.09						4L7,9
687.3	687.5	0.2	3287	26.0		1.54	1.13	2.67		0.24						4A7,4
687.5	689.6	2.1	3288	67.0		5.10	4.64	9.74		0.27						4G4,8
689.6	691.6	2.0	3289	2.0		0.03	0.04	0.07		0.02						4L3,7
691.6	693.6	2.0	3290	2.0		0.02	0.02	0.04		0.02						4L3,7
693.6	694.9	1.3	3291	1.0		0.04	0.03	0.07		0.03						4L3,7
694.9	696.9	2.0	3292	1.0		0.08	0.04	0.12		0.08						4L7
710.8	712.1	1.3	3368	1.0		0.07	0.06	0.13		0.05						4L3
712.1	714.3	2.2	3369	15.0		1.43	4.56	5.99		0.14						4C0,7
714.3	715.7	1.4	3370	TR		0.09	0.21	0.30		0.02						4L3
715.7	716.9	1.2	3371	TR		0.07	0.04	0.11		0.17						4C7,9
716.9	719.9	3.0	3372	TR		0.10	0.21	0.31		0.02						4L3
719.9	721.1	1.2	3373	18.0		1.31	4.61	5.92		0.60						4C0
721.1	722.3	1.2	3374	13.0		0.90	0.63	1.53		0.27						4E0
732.5	734.0	1.5	3375	4.0		0.20	0.34	0.54		0.10						4A0
734.0	735.1	1.1	3376	11.0		0.94	0.31	1.25		0.24						4C0
735.1	735.4	0.3	3377	TR		0.09	0.07	0.16		0.06						4L0
735.4	735.7	0.3	3378	17.0		1.39	0.47	1.86		0.31						4C0

GEOCHEMICAL LOG

Page 2 of 3

DY 79-X-16

<u>From</u>	<u>To</u>	<u>Int.</u>	<u>Samp. No.</u>	<u>Ag/AA GMS/MT</u>	<u>Ag/FA GMS/MT</u>	<u>Pb %</u>	<u>Zn %</u>	<u>Pb+Zn %</u>	<u>S.G.</u>	<u>Cu %</u>	<u>BaO %</u>	<u>Au GMS/MT</u>	<u>Po %</u>	<u>Py %</u>	<u>Hg %</u>	<u>Unit</u>
805.0	805.3	0.3	3379	90.0		6.80	9.78	16.58		0.11						4G4
805.3	805.7	0.4	3380	4.0		0.26	0.01	0.27		0.10						4H0
805.7	806.8	1.1	3381	TR		0.13	0.14	0.27		0.01						5B0,9
806.8	808.6	1.8	3382	19.0		1.57	0.34	1.91		0.31						?
808.6	809.1	0.5	3383	70.0		6.34	8.41	14.75		0.09						4G4
809.1	811.5	2.4	3384	33.0		2.04	1.33	3.37		0.21						4C0
811.5	811.8	0.3	3385	129.0		7.07	9.86	16.93		0.03						4G4
811.8	812.5	0.7	3386	90.0		6.00	8.18	14.18		0.11						4E0
812.5	812.9	0.4	3387	73.0		4.55	7.31	11.86		0.11						4G0
812.9	814.4	1.5	3388	120.0		7.55	8.18	15.73		0.09						4G4
814.4	815.5	1.1	3389	92.0		6.26	8.79	15.05		0.08						4D4/4G4
815.5	816.4	0.9	3390	108.0		8.51	6.50	15.01		0.07						4G4/0
816.4	817.8	1.4	3391	86.0		6.50	5.80	12.30		0.03						4D4
817.8	819.9	2.1	3392	98.0		5.15	8.06	13.21		0.05						4G4
819.9	820.2	0.3	3393	60.0		3.80	5.16	8.96		0.24						4H0
830.6	832.7	2.1	3394	26.0		1.40	1.73	3.13		0.04						4L4,2
832.7	833.9	1.2	3395	25.0		1.24	1.84	3.08		0.04						4L3
836.9	837.2	0.3	3396	139.0		4.22	6.27	10.49		0.16						4E7
840.4	841.7	1.3	3397	40.0		2.45	5.02	7.47		0.03						4A4
841.7	842.9	1.2	3398	31.0		1.81	3.36	5.17		0.03						4A0
842.9	843.5	0.6	3399	78.0		4.42	5.23	9.65		0.23						4E0
843.5	844.0	0.5	3400	54.0		3.17	4.99	8.16		0.06						4A0
844.0	845.1	1.1	3401	47.0		2.47	3.65	6.12		0.14						4C0
845.1	847.1	2.0	3402	52.0		2.74	5.64	8.38		0.12						4A0
847.1	849.1	2.0	3403	27.0		1.84	3.26	5.10		0.05						4A0
849.1	851.1	2.0	3404	21.0		1.60	3.46	5.06		0.04						4A0
851.1	853.1	2.0	3405	35.0		2.37	3.95	6.32		0.06						4A0
853.1	855.1	2.0	3406	27.0		1.77	3.68	5.45		0.04						4A0
855.1	857.0	1.9	3407	30.0		1.77	2.41	4.18		0.04						4A0
857.0	858.2	1.2	3408	16.0		0.82	1.78	2.60		0.02						4L4

79-X-17

79-X-17

CYPRUS ANVIL MINING CORPORATION

Page 1 of 1

GEOCHEMICAL LOG

Kamloops Research and Assay Lab.

<u>From</u>	<u>To</u>	<u>Int.</u>	<u>Sample No.</u>	<u>Ag/AA GMS/MT</u>	<u>Ag/FA GMS/MT</u>	<u>Pb %</u>	<u>Zn %</u>	<u>Pb+Zn %</u>	<u>S.G.</u>	<u>Cu %</u>	<u>BaO %</u>	<u>Au GMS/MT</u>	<u>Po %</u>	<u>Py %</u>	<u>Unit</u>
526.8	527.9	1.1	3334	73.0		3.73	6.83	10.56		0.02					4H4
527.9	529.2	1.3	3335	40.0		2.27	7.16	9.43		TR					4G4
529.2	530.0	0.8	3336	26.0		1.32	3.05	4.37		0.04					4H4
530.0	531.3	1.3	3337	26.0		1.88	5.41	7.29		TR					4G0
531.3	533.0	1.7	3338	17.0		0.87	1.74	2.61		0.05					4H0

79-X-18

GEOCHEMICAL LOG

Kamloops Research and Assay Lab.

From	To	Int.	Sample No.	Ag/AA GMS/MT	Ag/FA GMS/MT	Pb %	Zn %	Pb+Zn %	S.G.	Cu %	BaO %	Au GMS/MT	Po %	Py %	Unit
627.1	629.1	2.0	3463	1.0		0.03	0.01			0.01					4L7,3
629.1	631.1	2.0	3464	1.0		0.06	0.02			0.02					4L7,3
631.1	633.9	2.8	3465	3.0		0.20	0.16			0.07					4L7,3
633.9	634.2	0.3	3466	16.0		1.45	1.18	2.63		0.18					4C7
634.2	634.9	0.7	3467	38.0		3.04	1.41	4.45		0.24					4C7,8
634.9	637.1	2.2	3468	37.0		2.18	1.53	3.71		0.26					4C8
637.1	637.6	0.5	3469	26.0		1.27	1.34	2.61		0.41					4E0
637.6	638.2	0.6	3470	80.0		4.34	6.71	11.05		0.23					4G4
638.2	638.8	0.6	3471	18.0		0.52	0.19			0.26					4C8
638.8	639.4	0.6	3472	19.0		0.27	0.20			0.34					4E8
639.4	640.4	1.0	3473	9.0		0.24	0.13			0.20					4A0
640.4	643.1	2.7	3474	10.0		0.21	0.22			0.36					4C7
643.1	645.1	2.0	3475	9.0		0.24	0.16			0.35					4C7
645.1	647.1	2.0	3476	10.0		0.11	0.04			0.45					4C7
647.1	649.1	2.0	3477	6.0		0.10	0.04			0.20					4C7
649.1	651.1	2.0	3478	3.0		0.06	0.02			0.16					4C7
651.1	651.5	0.4	3479	3.0		0.13	0.02			0.11					4A0
651.5	653.5	2.0	3480	TR		0.06	0.06			0.02					4L7
653.5	654.4	0.9	3481	TR		0.23	0.13			0.04					4L7
654.4	654.8	0.4	3482	75.0		7.94	7.22	15.16		0.06					4D4
654.8	656.2	1.4	3483	52.0		3.60	4.55	8.15		0.19					4G0
656.2	656.8	0.6	3484	22.0		1.74	1.31	3.05		0.19					4H4/4L7
656.8	657.5	0.7	3485	35.0		2.00	1.45	3.45		0.24					4H4
657.5	658.1	0.6	3486	13.0		0.74	0.13	0.87		0.28					4C8
658.1	658.5	0.4	3487	20.0		1.41	0.96	2.37		0.17					4G4
658.5	659.4	0.9	3488	21.0		0.60	0.18	0.78		0.29					4C0
659.4	659.9	0.5	3489	41.0		2.89	7.14	10.03		0.09					4G4
659.9	660.8	0.9	3490	3.0		0.24	0.32	0.56		0.02					5D0
660.8	662.3	1.5	3491	61.0		4.59	7.39	11.98		0.08					4G4
662.3	662.8	0.5	3492	64.0		1.85	2.40	4.25		0.17					4E1
662.8	663.4	0.6	3493	32.0		1.43	2.76	4.19		0.06					4A4/4E0
663.4	663.7	0.3	3494	48.0		4.04	0.60	4.64		0.03					4D0
663.7	665.7	2.0	3495	47.0		4.78	1.96	6.74		0.10					4A0
665.7	668.5	2.8	3496	40.0		4.43	0.71	5.14		0.18					4A0

GEOCHEMICAL LOG

79-X-18

Page 2 of 2

<u>From</u>	<u>To</u>	<u>Int.</u>	<u>Sample No.</u>	<u>Ag/AA GMS/MT</u>	<u>Ag/FA GMS/MT</u>	<u>Pb %</u>	<u>Zn %</u>	<u>Pb+Zn %</u>	<u>S.G.</u>	<u>Cu %</u>	<u>BaO %</u>	<u>Au GMS/MT</u>	<u>Po %</u>	<u>Py %</u>	<u>Unit</u>
668.5	670.5	2.0	3497	8.0		0.11	0.09			0.14					4C0
670.5	671.7	1.2	3498	7.0		0.25	0.37			0.04					4C0
694.4	694.9	0.5	3499	5.0		0.37	0.31	0.68		0.28					4L3
694.9	695.4	0.5	3500	19.0		1.56	1.36	2.92		0.43					4E0/4H0
738.0	738.6	0.6	3501	57.0		2.98	6.97	9.95		0.04					4A4
738.6	740.5	1.9	3502	86.0		2.57	3.66	6.23		0.18					4D0
740.5	741.2	0.7	3503	116.0		3.17	4.44	7.61		0.20					4E1
741.2	741.9	0.7	3504	138.0		5.50	11.44	16.94		0.15					4G0
741.9	743.9	2.0	3505	44.0		2.27	6.21	8.48		0.01					4A4
743.9	744.8	0.9	3506	42.0		2.48	4.69	7.17		0.02					4A4
744.8	746.8	2.0	3507	30.0		1.71	3.21	4.92		0.06					4A0
746.8	748.8	2.0	3508	22.0		1.43	2.04	3.47		0.03					4A0
748.8	750.8	2.0	3509	18.0		1.29	1.36	2.65		0.02					4A0
750.8	752.8	2.0	3510	5.0		0.56	0.51	1.07		0.05					4A0
752.8	754.8	2.0	3511	8.0		0.78	0.78	1.56		0.04					4A0
754.8	755.3	0.5	3512	TR		0.28	0.04	0.32		0.01					4A0
759.5	760.0	0.5	3513	TR		0.24	0.21			0.02					4A0/4L0
760.0	762.2	2.2	3514	TR		0.11	0.03			TR					4A0
762.2	763.5	1.3	3515	TR		0.11	0.10			TR					4L0
763.5	765.8	2.3	3516	TR		0.09	0.15			0.01					4L3,7

BEST SECTION:

738.0	744.8	6.8		73.7		2.87	5.72	8.59							
(which includes)															
741.2	743.9	2.7		68.4		3.11	7.56	10.67							