

CYPRUSMINE LSA

ANVIL VCR

10/8/74

TO: R E THURMOND

FROM: J G SIMPSON

015847

FOLLOWING SUMMARY OF ASSAY RESULTS TO DATE EARN PROJECT. READ
PERCENT CU PERCENT PB PERCENT ZN OZ AG:

DDH 466-74-1

32 TO 120 FT, 88 FT AT	0.18,	0.15,	1.0,	0.34 ³
210 TO 250 FT, 40 FT AT	0.14,	0.53,	0.9,	1.56
270 TO 290 FT, 20 FT AT	0.20,	0.37,	1.0,	0.93

AVERAGE 148 FT 0 TO 290 FT 0.17, 0.28, 0.97, 0.80

DDH 466-74-2

8 TO 66 FT, 58 FT AT	0.20,	1.08,	1.75,	TO COME #30
94 TO 140 FT, 46 FT AT	0.16,	0.10,	1.47,	TO COME
154 TO 294 FT, 140 FT AT	0.08,	0.17,	1.11,	TO COME

	80	.16	.24	
--	----	-----	-----	--


AVERAGE 244 FT FROM 0 TO 294 FT 0.12, 0.38, 1.33 TO COME

■ TO BE CHECKED AG ASSAYS 210 - 290 FT IN DDH 466-74-1 INDICATE
RATIO OZ AG TO PERCENT PB IS 3 TO 1 FIGURE OF 0.84 REDUCED TO
0.45 FOR AVERAGE. ANTICIPATE ABOUT ONE OZ AG FOR ASSAY SECTIONS
DDH-74-2.

MONTHLY REPORT FOR SEPT MAILED AM TODAY.

*

CYPRUSMINE LSA



BONDAR-CLEGG & COMPANY LTD.

764 BELFAST ROAD, OTTAWA, ONTARIO, K1G 0Z5 PHONE: 237-3110 TELEX: 053-3548

JAKE

PETE LEWIS PUT THESE samples in for GRES
Some Dona samples

AC 466

Certificate of Analysis

TO Anvil Mining Corporation
Exploration Department
Box 1000
Faro, Y.T.

REPORT NO. A 44-23

EARN
DANA/HAL

DATE July 11, 1974

I hereby certify that the following are the results of analyses made by us upon the herein described rock samples

MARKED	Cu	Pb	Zn	Au	Ag	As ppm				
	%	%	%							
EA*1 16826	0.01	LO.02	0.04			50				
EA2 16827	LO.01	LO.02	0.01			15				
EA3 16828	LO.01	0.03	LO.01							
EA4 16829	0.01	LO.02	0.01							
EA5 16830	LO.01	LO.02	LO.01							
EA6 16831	0.01	0.11	0.06		0.17					
EA7 16832	0.01	0.13	0.16		0.02					
EA8 16833	0.05	0.21	0.30	tr	0.22					
EA9 16834	0.05	0.28	0.39	tr						
EA10 16835	0.01	9.40	0.07	tr	9.5					
EB1 16836	0.35	0.15	0.67	tr	tr					
EB2 16837	0.25	0.41	0.39	tr	3.7					

BONDAR-CLEGG & COMPANY LTD.

NOTE:

Rejects retained two weeks
Pulps retained three months
unless otherwise arranged

R. A. Pittuck Chief Chemist

JAVE

AC 466

NOTE: REJECTS FOR THESE
samples in far BAGS
From Dana samples

Certificate of Analysis

TO Anvil Mining Corporation
Exploration Department
Box 1000
Faro, Y.T.

EARN
DANA/HAL

REPORT NO. A 44-23
DATE July 11, 1974

I hereby certify that the following are the results of analyses made by us upon the herein described rock samples

MARKED	Cu	Pb	Zn	Cu	Pb	Zn	Ag	Au	AS	Ref/PB
	%	%	%	ppm	ppm	ppm	ppm	ppb	ppm	
EA#1 16826	0.01	0.02	0.04	116	39	375	2.6	-	80	rusty weath pyritic chert tube chert Sulfate gangue sulphide rich matrix? gossan
EA2 16827	0.01	0.02	0.01	85	28	100	60	-	13	
EA3 16828	0.01	0.03	0.01	18	242	26	-	-	-	
EA4 16829	0.01	0.02	0.01	122	58	88	1.2	-	60	
EA5 16830	0.01	0.02	0.01	26	30	30	-	-	-	
EA6 16831	0.01	0.11	0.06				0.170% tr	-	-	
EA7 16832	0.01	0.13	0.16				0.020% tr	-	-	1.54 Pb boulder at SS stain from
EA8 16833	0.05	0.21	0.30				0.220% tr	-	-	-15 Area A Pb w/ls below chert
EA9 16834	0.05	0.28	0.39				- tr	-	-	1.05 Area A chert Aspy rich sample chert
EA10 16835	0.01	9.40	0.07				9.500% tr	-	-	1.01 Eds grab
EB1 16836	0.35	0.15	0.67				tr tr	-	-	very low Dana chert w/
EB2 16837	0.25	0.41	0.39				3.700% tr	-	-	9.04 Dana chert E

NOTE:
Rejects retained two weeks
Pulps retained three months
unless otherwise arranged.

BONDAR-CLEGG & COMPANY LTD.

R. A. Pittuck
R. A. Pittuck Chief Chemist



Certificate of Analysis

TO Anvil Mining Corp.
Exploration Department
Box 1000
Faro, Y.T.

REPORT NO. A 44-40


DATE August 5, 1974

I hereby certify that the following are the results of analyses made by us upon the herein described pulp samples

MARKED	Au	Ag							
	oz/ton	oz/ton							
16831		0.17							
16832		0.02							
16833	Trace	0.22							
16834	Trace								
16835	Trace	9.5							
16836	Trace	Trace							
16837	Trace	3.7							

NOTE:
Rejects retained two weeks
Pulps retained three months
unless otherwise arranged.

BONDAR-CLEGG & COMPANY LTD.



BONDAR-CLEGG & COMPANY LTD.

764 BELFAST ROAD, OTTAWA, ONTARIO, K1G 0Z5 PHONE: 237-3110 TELEX: 053-3548

Certificate of Analysis

EARN 466 FILE.

TO Anvil Mining Exploration Dept.
Box 1000
Faro, Y.T.

REPORT NO. A 44-85

DATE August 21, 1974

I hereby certify that the following are the results of analyses made by us upon the herein described Rock samples


MARKED	Cu	Pb	Zn						
	%	%	%						
EB-90	0.16	5.16	0.45						
EB-91	1.06	0.45	2.88						
EB-92	0.39	0.12	9.72						
Au and Ag results to follow									

BONDAR-CLEGG & COMPANY LTD.

NOTE:

Rejects retained two weeks
Pulps retained three months
unless otherwise arranged

[Signature]
R. A. Pittuck Chief Chemist



BONDAR-CLEGG & COMPANY LTD.

764 BELFAST ROAD, OTTAWA, ONTARIO, K1G 0Z5 PHONE: 237-3110 TELEX: 053-3548

Certificate of Analysis

EARN 466 FILE

TO Anvil Mining Exploration Dept.
Box 1000
Faro, Y.T.

REPORT NO. A.44-85

DATE August 21, 1974

I hereby certify that the following are the results of analyses made by us upon the herein described Rock samples

MARKED	Cu	Pb	Zn						
	%	%	%						
EB-90 <i>28 chip</i>	0.16	5.16	0.45						
EB-91 <i>325 chip</i>	1.06	0.45	2.88						
EB-92 <i>245 grab</i>	0.39	0.12	9.72	<i>Greg</i>	<i>my grab sample of high grade. Glenn</i>				
Au and Ag results to follow									

NOTE:

Rejects retained two weeks
Pulps retained three months

BONDAR-CLEGG & COMPANY LTD.

To: _____

REPORT No. A44 - 85

PAGE No. One


BONDAR-CLEGG & COMPANY LTD.

DATE: August 28, 1974

CERTIFICATE OF ASSAY

I hereby certify that the following are the results of assays made by us upon the herein described Rock samples.

MARKED	GOLD		SILVER								TOTAL VALUE PER TON (2000 LBS.)
	Ounces per Ton	Value per Ton	Ounces per Ton	Percent	Percent	Percent	Percent	Percent	Percent		
EB 90	0.005		4.6								
EB 91	Trace		2.7								
EB 92	0.005		0.04								


 Registered Assayer, Province of British Columbia
R. A. Pittuck Chief Chemist

To: _____

REPORT No. A 44-93

PAGE No. One

BONDAR-CLEGG & COMPANY LTD.

DATE: August 29, 1974

Anvil Mining Corp.
Faro, Y.T.

CERTIFICATE OF ASSAY

I hereby certify that the following are the results of assays made by us upon the herein described **Rock** samples.

MARKED	GOLD		SILVER	Pb	Zn						TOTAL VALUE PER TON (2000 LBS.)
	Ounces per Ton	Value per Ton	Ounces per Ton	Percent	Percent	Percent	Percent	Percent	Percent		
16357			0.29	0.59	0.16						
16358			0.18	0.24	0.15						
16359			0.29	0.44	0.30						
16360			0.53	1.60	0.12						
16361			0.47	1.20	0.05						
16362			0.18	0.41	0.09						
16373			0.06	0.01	0.26						
16394			0.29	0.37	0.58						
16801			0.12	0.08	0.57						


 Registered Assayer Province of British Columbia
 R. A. Pittuck Chief Chemist



BONDAR-CLEGG & COMPANY LTD.

764 BELFAST ROAD, OTTAWA, ONTARIO, K1G 0Z5 PHONE: 237-3110 TELEX: 053-3548

Certificate of Analysis

TO Cyprus-Anvil Mining Corp. Ltd.
Box 1000
Faro, Y.T.

REPORT NO. A44 -125

DATE October 3, 1974

I hereby certify that the following are the results of analyses made by us upon the herein described drill core samples

MARKED	%	%	%	oz/ton	oz/ton				
	Cu	Pb	Zn	Ag	check Ag				
32-40 9326	0.45	0.08	2.76	0.864	0.18				
40-50 9327	0.15	0.17	0.26	0.876	0.25				
50-60 9328	0.06	0.11	0.99	0.548	0.04				
60-70 9329	0.09	0.46	0.82	2.29*	1.60				
70-80 93300	0.05	0.06	0.06	0.368	0.10				
80-90 9331	0.11	0.31	0.14	1.04	0.90				
90-100 9332	0.36	0.05	1.20	0.654	0.15				
100-110 9333	0.25	0.02	2.32	0.542	0.17				
110-120 9334	0.11	0.05	0.79	0.397	0.18				
EB93	0.48	8.80	3.88	11.69*	6.60				

*.Ag values for 9329, EB93 to be checked by Vancouver lab.

NOTE:

Rejects retained two weeks
Pulps retained three months
unless otherwise arranged.

✓ ✓ ✓

✓ BONDAR-CLEGG & COMPANY LTD.

A.D. Sinclair

CERTIFICATE OF ANALYSIS


TO
 *CYPRUS ANKIL*

REPORT NO. *A-44-126*
 DATE ... *Sept. 27, 1974* ...
Part 1.

I hereby certify that the following are the results of analyses made by us upon the herein described *drill core* samples

MARKED	%	%	%									
	<i>Cu</i>	<i>Pb</i>	<i>Zn</i>									
<i>9335</i>	<i>0.06</i>	<i>0.13</i>	<i>0.40</i>									
<i>36</i>	<i>.10</i>	<i>.11</i>	<i>.79</i>									
<i>37</i>	<i><.01</i>	<i>.02</i>	<i>.05</i>									
<i>9343</i>	<i><.01</i>	<i>.03</i>	<i>.03</i>									
<i>44</i>	<i>.09</i>	<i>.54</i>	<i>1.44</i>									
<i>9345</i>	<i>.07</i>	<i>.15</i>	<i>.68</i>									
<i>46</i>	<i>.02</i>	<i>.07</i>	<i>.42</i>									
<i>47</i>	<i>.37</i>	<i>1.38</i>	<i>1.08</i>									
<i>48</i>	<i>.04</i>	<i>.03</i>	<i>.05</i>									
<i>49</i>	<i>.03</i>	<i>.13</i>	<i>.05</i>									
<i>9350</i>	<i>.23</i>	<i>0.68</i>	<i>.80</i>									
<i>51</i>	<i>.18</i>	<i>.07</i>	<i>2.20</i>									
<i>52</i>	<i>.08</i>	<i>.05</i>	<i>.50</i>									
<i>53</i>	<i>.03</i>	<i>.04</i>	<i>.05</i>									

REMARKS: *all Ag's will be done by P.D. Smith*
Vancouver lab.
Rest of report + typed copy + invoice to follow.



BONDAR-CLEGG & COMPANY LTD.

764 BELFAST ROAD, OTTAWA, ONTARIO, K1G 0Z5 PHONE: 237-3110 TELEX: 053-3548

Certificate of Analysis

TO Cyprus-Anvil Mining Corp. Ltd.
Box 1000
Faro, Y.T.

REPORT NO. **A44 -125**

DATE **October 3, 1974**

I hereby certify that the following are the results of analyses made by us upon the herein described **drill core** samples

MARKED	%	%	%	oz/ton					
	Cu	Pb	Zn	Ag					
9326	0.45	0.08	2.76	0.864					
9327	0.15	0.17	0.26	0.876					
9328	0.06	0.11	0.99	0.548					
9329	0.09	0.46	0.82	2.29*					
9330	0.05	0.06	0.06	0.368					
9331	0.11	0.31	0.14	1.04					
9332	0.36	0.05	1.20	0.654					
9333	0.25	0.02	2.32	0.542					
9334	0.11	0.05	0.79	0.397					
EB93	0.48	8.80	3.88	11.69*					

*.Ag values for 9329, EB93 to be checked by Vancouver lab.

BONDAR-CLEGG & COMPANY LTD.

NOTE:

Rejects retained two weeks
Pulps retained three months
unless otherwise arranged.

[Handwritten signature]

VMTD

D+
ANVIL VCR

ANVIL VCR

ATTEN J G SIMOSON

OUR REPORT A44-125

PERCENT CU	PERCENT PB	PERCENT ZN	PERCENT ON
			CORR OUNCE PER TON
9326	0.45		

:9443:589, 28)) '5-45 9=34 -8-8,
CORRECTION WILL START OVER AGAIN

	PERCENT CU	PERCENT PB	PERCENT ZN	ONCE PER TON
0				
9326	0.25			

CORR	cu	Pb.	Zn	Ag	
9326	0.45	0.08	2.76	0.864	
9327	0.15	0.17	0.26	0.876	
9328	0.06	0.11	0.99	0.548	
9329	0.09	0.46	0.82	2.29	
9330	0.05	0.06	0.06	0.368	
9331	0.11	0.31	0.14	1.04	
9332	0.36	0.05	1.20	0.654	
93333	0.25	0.02	2.23	0.542	
9334	0.11	0.05	0.79	0.9CORR	P 0.39
	<u>9.163</u>	<u>1.31</u>	<u>9.25</u>	<u>0.397</u>	
EB93	0.48	8.80	3.88	<u>11.69</u>	
AG VALUES	9329 EB93 TO BE CHECKED BY VCR LAB			7.579	
	.18	.14	1.02		

P D SINCLAIR BONDAR CLEGG



BONDAR-CLEGG & COMPANY LTD.

764 BELFAST ROAD, OTTAWA, ONTARIO, K1G 0Z5 PHONE: 237-3110 TELEX: 053-3548

Certificate of Analysis

TO Cyprus-Anvil Mining Corp. Ltd.

REPORT NO. A44-126

DATE October 3, 1974

I hereby certify that the following are the results of analyses made by us upon the herein described drill core samples

MARKED		%	%	%						
#		Cu	Pb	Zn						
120-130	9335	0.06	0.13	0.40	}	0.27				
130-140	9336	0.10	0.11	0.79		0.29				
140-150	9337	<0.01	0.03	0.03		0.04				
200-210	9343	<0.01	0.03	0.03		0.12				
210-220	9344	0.09	0.54	1.44		0.85				
220-230	9345	0.07	0.15	0.68	}	0.42				
230-240	9346	0.02	0.07	0.42		0.06				
240-250	9347	0.37	1.38	1.08		4.90				
250-260	9348	0.04	0.03	0.05		TR				
260-270	9349	0.03	0.13	0.05		0.35				
270-280	9350	0.23	0.68	0.80	}	1.60				
280-290	9351	0.18	0.07	2.20		0.37				
290-300	9352	0.08	0.05	0.50		0.18				
300-310	9353	0.03	0.04	0.05		0.32				
310-320	9354	0.03	0.12	0.01		0.38				
320-330	9355	0.03	0.05	0.40	}	0.25				
330-340	9356	0.07	0.04	1.05		0.24				

BONDAR-CLEGG & COMPANY LTD.

NOTE:

Rejects retained two weeks
Pulps retained three months
unless otherwise arranged.

✓ ✓ ✓ ✓

Dr. *P.D. Sinclair*, Chief Chemist



Certificate of Analysis

Page 2

TO Cyprus=Anvil

REPORT NO. A44-126

DATE

I hereby certify that the following are the results of analyses made by us upon the herein described samples

MARKED	%	%	%						
	Cu	Pb	Zn						
340-350 9357	0.05	0.08	0.29	} 0.35 0.02 0.02 0.02 0.02					
350-360 9358	0.06	0.16	0.30						
360-370 9359	0.10	0.06	0.25						
370-380 9360	0.22	0.05	4.20						
380-390 9361	0.03	0.05	0.13						
390-400 9362	0.11	0.30	1.10	} 0.67 0.77 0.28					
9376	0.30	0.20	0.99						
9377	0.06	0.10	0.21						
Ag values to follow									

BONDAR-CLEGG & COMPANY LTD.

NOTE:
Rejects retained two weeks
Pulps retained three months
unless otherwise arranged.

✓ ✓ ✓ ✓

CERTIFICATE OF ANALYSIS

TO
Cyprus Anvil

REPORT NO. *A-44-126*

DATE ... *Sept. 27, 1974* ..
Part 1.

I hereby certify that the following are the results of analyses made by us upon the herein described *drill core* samples

MARKED	%	%	%								
	<i>Cu</i>	<i>Pb</i>	<i>Zn</i>								
<i>9335</i>	<i>0.06</i>	<i>0.13</i>	<i>0.40</i>								
<i>36</i>	<i>.16</i>	<i>.11</i>	<i>.79</i>								
<i>37</i>	<i><.01</i>	<i>.02</i>	<i>.05</i>								
<i>9343</i>	<i><.01</i>	<i>.03</i>	<i>.03</i>								
<i>44</i>	<i>.09</i>	<i>.54</i>	<i>1.44</i>								
<i>9345</i>	<i>.07</i>	<i>.15</i>	<i>.68</i>								
<i>46</i>	<i>.02</i>	<i>.07</i>	<i>.42</i>								
<i>47</i>	<i>.37</i>	<i>1.38</i>	<i>1.08</i>								
<i>48</i>	<i>.04</i>	<i>.03</i>	<i>.05</i>								
<i>49</i>	<i>.03</i>	<i>.13</i>	<i>.05</i>								
<i>9350</i>	<i>.23</i>	<i>0.68</i>	<i>.80</i>								
<i>51</i>	<i>.18</i>	<i>.07</i>	<i>2.20</i>								
<i>52</i>	<i>.08</i>	<i>.05</i>	<i>.50</i>								
<i>53</i>	<i>.03</i>	<i>.04</i>	<i>.05</i>								

REMARKS: *All Ag's will be done by Vancouver lab.*
Rest of report + typed copy + invoice to follow.

A.D. Sinclair



BONDAR-CLEGG & COMPANY LTD.

764 BELFAST ROAD, OTTAWA, ONTARIO, K1G 0Z5 PHONE: 237-3110 TELEX: 053-3548

Certificate of Analysis

TO J. G. Simpson
Cyprus Anvil

REPORT NO. A-44-126

DATE Sept. 30., 1974

I hereby certify that the following are the results of analyses made by us upon the herein described drill core samples

MARKED	%	%	%						
	Cu	Pb	Zn						
9335 120-130	0.06	0.13	0.40						
36 130-140	.10	.11	.79						
37 140-150	<.01	.02	.05						
43 200-210	<.01	.03	.03						
44 210-220	.09	.54	1.44						
9345 220-230	.07	.15	.68						
46 230-240	.02	.07	.42						
47 240-250	.37	1.38	1.08	*					
48 250-260	.04	.03	.05						
49 260-270	.03	.13	.05						
9350 270-280	.23	.68	.80	*					
51 280-290	.18	.07	2.20						
52 290-300	.08	.05	.50						
53 300-310	.03	.04	.05						
54 310-320	.03	.12	.01						

BONDAR-CLEGG & COMPANY LTD.

NOTE:

Rejects retained two weeks
Pulps retained three months
unless otherwise arranged

A. D. Smith



BONDAR-CLEGG & COMPANY LTD.

764 BELFAST ROAD, OTTAWA, ONTARIO, K1G 0Z5 PHONE: 237-3110 TELEX: 053-3548

Certificate of Analysis

TO U. Jansons
Cyprus. Anv. 1

REPORT NO. A-44-126

DATE Sept. 30 1974

I hereby certify that the following are the results of analyses made by us upon the herein described drill core samples

MARKED	%		%		%				
	Cu		Pb		Zn				
9335	0.06		0.13		0.40				
36	.10		.11		.79				
37	< .01		.02		.05				
43 43	< .01		.03		.03				
44	.09		.54		1.44				
9345	.07		.15		.68				
46	.02		.07		.42				
47	.37		1.38		1.08				
48	.04		.03		.05				
49	.03		.13		.05				
9350	.23		.68		.80				
51	.18		.07		2.20				
52	.08		.05		.50				
53	.03		.04		.05				
54	.03		.12		.01				

BONDAR-CLEGG & COMPANY LTD.

NOTE:

Rejects retained two weeks
Pulps retained three months
unless otherwise arranged.

S. D. Sinclair



BONDAR-CLEGG & COMPANY LTD.

764 BELFAST ROAD, OTTAWA, ONTARIO, K1G 0Z5 PHONE: 237-3110 TELEX: 053-3548

Certificate of Analysis

TO J.G. Simpson
Cyprus - Anvil

REPORT NO. A-44-126

DATE Sept. 30, 1974

I hereby certify that the following are the results of analyses made by us upon the herein described drill core samples

MARKED	%	%	%					
	Cu	Pb	Zn					
#1 9355 320-330	0.03	0.05	0.40					
56 330-340	.07	.04	1.05					
57 340-350	.05	.08	.29					
58 350-360	.06	.16	.30					
59 360-370	.10	0.05 .06	.25	*				
9360 370-380	.22	.05	4.20	NP				
61 380-390	.03	.05	.13					
62 390-400	.11	.30	1.10					
76 410 530-540	.30	.20	.99	*				
77 540-550	.06	.10	.21					

BONDAR-CLEGG & COMPANY LTD.

NOTE:

Rejects retained two weeks
Pulps retained three months
unless otherwise arranged

P.D. Sinclair



Certificate of Analysis

TO V. Jansons
Cyprus - Arvil

REPORT NO. 11-44-126
DATE Sept 30, 1974

I hereby certify that the following are the results of analyses made by us upon the herein described drill core samples


MARKED	%	%	%						
	Cu	Pb	Zn						
9355	0.03	0.05	0.40						
56	.07	.04	1.05						
57	.05	.08	.29						
58	.06	.16	.30						
59	.10	0.05 .06	.25						
9360	.22	.05	4.20						
61	.03	.05	.13						
62	.11	.30	1.10						
76	.30	.20	.99						
77	.06	.10	.21						

BONDAR-CLEGG & COMPANY LTD.

NOTE:

Rejects retained two weeks
Pulps retained three months
unless otherwise arranged.

P.D. Sinclair



Certificate of Analysis

Caru

TO Cyprus-Anvil Mining Corp. Ltd.

REPORT NO. A44-126.....

DATE October 3, 1974.....

I hereby certify that the following are the results of analyses made by us upon the herein described **drill core**..... samples

MARKED	%	%	%						
	Cu	Pb	Zn						
9335	0.06	0.13	0.40						
9336	0.10	0.11	0.79						
9337	<0.01	0.03	0.03						
9343	<0.01	0.03	0.03						
9344	0.09	0.54	1.44						
9345	0.07	0.15	0.68						
9346	0.02	0.07	0.42						
9347	0.37	1.38	1.08						
9348	0.04	0.03	0.05						
9349	0.03	0.13	0.05						
9350	0.23	0.68	0.80						
9351	0.18	0.07	2.20						
9352	0.08	0.05	0.50						
9353	0.03	0.04	0.05						
9354	0.03	0.12	0.01						
9355	0.03	0.05	0.40						
9356	0.07	0.04	1.05						

BONDAR-CLEGG & COMPANY LTD.

NOTE:

Rejects retained two weeks
Pulps retained three months
unless otherwise arranged.

..... *P.D. Sinclair*
Dr. P.D. Sinclair, Chief Chemist



CYPRUS ANVIL MINING CORPORATION

Certificate of Analysis

Page 1

N.B. duplicate results

TO Mr. J.G. Simpson
Cyprus-Anvil Mining Corp. Ltd.
801 - 1550 Alberni St.

REPORT NO. A 44-125, A 44-126...
DATE October 21, 1974...
on A 24-766

Vancouver, B.C.

I hereby certify that the following are the results of analyses made by us upon the herein described... drill core..... samples

MARKED	oz/ton								
	Ag								
9329	1.6								
EB93	6.6								
9335	0.27								
9336	0.29								
9337	0.04								
9343	0.12								
9344	0.85								
9345	0.42								
9346	0.06								
9347	4.9								
9348	trace								
9349	0.35								
9350	1.6								
9351	0.37								
9352	0.18								
9353	0.32								
9354	0.38								

BONDAR-CLEGG & COMPANY LTD.

NOTE: Rejects retained two weeks
Pulps retained three months
unless otherwise arranged



P.D. Sinclair



Certificate of Analysis

Page 2

TO Cyprus-Anvil Mining Corp. Ltd.

REPORT NO. A. 44-125. A. 44-126.....

DATE October 21, 1974.....

I hereby certify that the following are the results of analyses made by us upon the herein described drill core..... samples

MARKED	oz/ton									
	Ag									
9355	0.25									
9356	0.24									
9357	0.35									
9358	0.02									
9359	0.02									
9360	0.02									
9361	0.02									
9362	0.67									
9376	0.77									
9377	0.28									

BONDAR-CLEGG & COMPANY LTD.

NOTE:

Rejects retained two weeks
Pulps retained three months
unless otherwise arranged.

A. D. Sinclair



Certificate of Analysis

Page 1

TO Mr. J.G. Simpson
Cyprus-Anvil Mining Corp. Ltd.
801 - 1550 Alberni St.

REPORT NO. A. 44-125, A. 44-126.....

DATE October 21, 1974.....

I hereby certify Vancouver, B.C. that the following are the results of analyses made by us upon the herein described drill core..... samples

MARKED	oz/ton								
	Ag								
9329	1.6								
EB93	6.6								
9335	0.27								
9336	0.29								
9337	0.04								
9342	0.12								
9344	0.85								
9345	0.42								
9346	0.06								
9347	4.9								
9348	trace								
9349	0.35								
9350	1.6								
9351	0.37								
9352	0.18								
9353	0.32								
9354	0.38								

BONDAR-CLEGG & COMPANY LTD.

NOTE:

Rejects retained two weeks
Pulps retained three months
unless otherwise arranged.

S.D. Sinclair.....



Certificate of Analysis

Page 2

TO Cyprus Anvil Mining Corp. Ltd.

REPORT NO. A 44-125. A 44-126

DATE October 21, 1974

I hereby certify that the following are the results of analyses made by us upon the herein described drill core samples

MARKED	oz/ton									
	Ag									
9355	0.25									
9356	0.24									
9357	0.35									
9358	0.02									
9359	0.02									
9360	0.02									
9361	0.02									
9362	0.67									
9376	0.77									
9377	0.28									

BONDAR-CLEGG & COMPANY LTD.

NOTE:

Rejects retained two weeks
Pulps retained three months
unless otherwise arranged.

A. D. Sinclair



BONDAR-CLEGG & COMPANY LTD.

764 BELFAST ROAD, OTTAWA, ONTARIO, K1G 0Z5 PHONE: 237-3110 TELEX: 053-3548

Certificate of Analysis

TO Mr. J.G. Simpson
Cyprus - Anvil

REPORT NO. A 44-129

DATE October 3, 1974

I hereby certify that the following are the results of analyses made by us upon the herein described drill core samples

MARKED	%	%	%						
	Cu	Pb	Zn						
9383	0.16	0.02	2.48	0.02					
9384	0.18	0.08	2.68	0.44					
9385	0.06	0.02	0.72	0.06					
9386	0.04	0.06	0.19	0.08					
9387	0.15	2.60	2.72	2.00					
9388	0.13	0.54	1.76	0.68					
9394	0.06	0.11	1.40	0.04					
9395	0.29	0.27	3.16	1.00					
9397	0.20	0.24	1.92	0.95					
9400	0.08	0.04	2.60	0.10					
				Ag results to follow					

BONDAR-CLEGG & COMPANY LTD.

NOTE:

Rejects retained two weeks
Pulps retained three months
unless otherwise arranged

J. S. Sclater
.....
D. P. Sclater, Chief Analyst



BONDAR-CLEGG & COMPANY LTD.

764 BELFAST ROAD, OTTAWA, ONTARIO, K1G 0Z5 PHONE: 237-3110 TELEX: 053-3548

Certificate of Analysis

TO Mr. J.G. Simpson
Cyprus - Anvil

REPORT NO. A 44-129

DATE October 3, 1974

I hereby certify that the following are the results of analyses made by us upon the herein described drill core samples

MARKED	%	%	%						
	Cu	Pb	Zn						
9383	0.16	0.02	2.48						
9384	0.18	0.08	2.68						
9385	0.06	0.02	0.72						
9386	0.04	0.06	0.19						
9387	0.15	2.60	2.72						
9388	0.13	0.54	1.76						
9394	0.06	0.11	1.40						
9395	0.29	0.27	3.16						
9397	0.20	0.24	1.92						
9400	0.08	0.04	2.60						
Ag results to follow									

BONDAR-CLEGG & COMPANY LTD.

NOTE:

Rejects retained two weeks
Pulps retained three months
unless otherwise arranged.

S. D. Jackson



Certificate of Analysis

TO Cyprus- Anvil Mining Corp.
801 - 1550 Alberni St.
Vancouver, B.C.

REPORT NO. ... A 44-131.....

DATE .. October 7, 1974.....


I hereby certify that the following are the results of analyses made by us upon the herein described .. drill .. core .. samples

MARKED	%	%	%						
	Cu	Pb	Zn						
9398	0.05	0.07	0.17	0.31					
9403	0.04	0.01	0.88	TR					
9404	0.06	0.08	1.56	0.31					
9405	0.72	1.55	4.00	7.0					
9406	0.32	2.60	4.80	7.4					
9407	0.08	0.63	0.81	1.5					
9408	0.10	0.75	0.81	0.96					
94101	0.08	0.19	1.30	1.10					
9411	0.10	0.06	0.86	0.25					
9415	0.31	2.60	2.24	2.1					
9417	0.07	0.11	1.30	0.16					
9418	0.06	0.06	0.79	0.04					Ag values to follow.
9419	0.73	0.26	4.56	1.10					
9422	0.09	0.05	1.80	0.19					
EB96	0.73	0.14	1.72	1.60					

BONDAR-CLEGG & COMPANY LTD.

NOTE:
 Rejects retained two weeks
 Pulps retained three months
 unless otherwise arranged.

P.D. Sinclair
 Dr. P.D. Sinclair, Chief Chemist



BONDAR-CLEGG & COMPANY LTD.

764 BELFAST ROAD, OTTAWA, ONTARIO, K1G 0Z5 PHONE: 237-3110 TELEX: 053-3548

Certificate of Analysis

TO Cyprus- Anvil Mining Corp.
801 - 1550 Alberni St.
Vancouver, B.C.

REPORT NO. . . . A 44-131

DATE . . . October 7, 1974

I hereby certify that the following are the results of analyses made by us upon the herein described . . . **drill core** samples

MARKED	%	%	%						
	Cu	Pb	Zn						
9398	0.05	0.07	0.17						
9303	0.04	0.01	0.88						
9404	0.06	0.08	1.56						
9405	0.72	1.55	4.00						
9406	0.32	2.60	4.80						
9407	0.08	0.63	0.81						
9408	0.10	0.75	0.81						
9410	0.08	0.19	1.30						
9411	0.10	0.06	0.86						
9415	0.31	2.60	2.24						
9417	0.07	0.11	1.30						
9418	0.06	0.06	0.79						
9419	0.73	0.26	4.56						
9422	0.09	0.05	1.80						
EB96	0.73	0.14	1.72						

Ag values to follow.

BONDAR-CLEGG & COMPANY LTD.

NOTE:

Rejects retained two weeks
Pulps retained three months
unless otherwise arranged

P. D. Sinclair



BONDAR-CLEGG & COMPANY LTD.

764 BELFAST ROAD, OTTAWA, ONTARIO, K1G 0Z5 PHONE: 237-3110 TELEX: 053-3548

Certificate of Analysis

TO Cyprus-Anvil Mining Corp. Ltd.
801 - 1550 Alberni St.
Vancouver, B.C.

REPORT NO. ... A. 44-132

DATE October 9, 1974

I hereby certify that the following are the results of analyses made by us upon the herein describeddrill core... samples

MARKED	%	%	%						
	Cu	Pb	Zn						
9391	0.02	0.05	0.05						
92	0.05	0.18	0.13						
93	0.04	0.09	0.11						
99	0.02	0.06	0.24						
9401	0.01	0.01	0.05						
9409	0.03	0.03	0.49						
12	0.03	0.12	0.19 ^o						
14	0.05	0.20	0.12						
16	0.12	0.27	0.33						
28	0.16	0.15	2.04						
9430	0.26	0.47	1.88						
32	0.11	0.11	0.61						
34	0.17	0.03	0.64						
35	0.31	0.05	1.09						
39	0.68	0.14	0.87						
9440	1.72	0.16	4.64						
41	0.30	0.07	0.24						

NOTE:
Rejects retained two weeks
Pulps retained three months
unless otherwise arranged

✓ ✓ ✓

BONDAR-CLEGG & COMPANY LTD.

A.D. Sinclair



Certificate of Analysis

Page 2

TO Cyprus- Anvil Mining Corp.

REPORT NO. A 44 -132

DATE

I hereby certify that the following are the results of analyses made by us upon the herein described drill core samples


MARKED	%	%	%						
	Cu	Pb	Zn						
9444	0.08	0.04	0.22						
9445	0.13	0.05	0.45						
9449	0.02	0.01	0.71						
9451	0.14	0.04	1.54						
9452	0.02	0.01	0.54						
9453	0.05	0.01	0.79						
9454	0.07	0.01	1.30						
9455	0.05	0.01	0.71						
9456	0.23	<0.01	5.28						
9457	0.04	<0.01	0.57						
9458	0.14	0.01	4.40						
Ag results to follow.									

BONDAR-CLEGG & COMPANY LTD.

NOTE:

Rejects retained two weeks
Pulps retained three months
unless otherwise arranged

✓ ✓ ✓



BONDAR-CLEGG & COMPANY LTD.

764 BELFAST ROAD, OTTAWA, ONTARIO, K1G 0Z5 PHONE: 237-3110 TELEX: 053-3548

Certificate of Analysis

TO Cyprus-Anvil Mining Corp. Ltd.
801 - 1550 Alberni St.
Vancouver, B.C.

REPORT NO. . . . A 44-132

DATE October 9, 1974

I hereby certify that the following are the results of analyses made by us upon the herein described **drill core** . . . samples

MARKED	%	%	%						
	Cu	Pb	Zn						
9391	0.02	0.05	0.05						
92	0.05	0.18	0.13						
93	0.04	0.09	0.11						
99	0.02	0.06	0.24						
9401	0.01	0.01	0.05						
9409	0.03	0.03	0.49						
12	0.03	0.12	0.19						
14	0.05	0.20	0.12						
16	0.12	0.27	0.33						
28	0.16	0.15	2.04						
9430	0.26	0.47	1.88						
32	0.11	0.11	0.61						
34	0.17	0.03	0.64						
35	0.31	0.05	1.09						
39	0.68	0.14	0.87						
9440	1.72	0.16	4.64						
41	0.30	0.07	0.24						

BONDAR-CLEGG & COMPANY LTD.

NOTE:

Rejects retained two weeks
Pulps retained three months
unless otherwise arranged.

[Handwritten signature]



Certificate of Analysis

Page 2

TO Cyprus- Anvil Mining Corp.

REPORT NO. A 44 -132

DATE

I hereby certify that the following are the results of analyses made by us upon the herein described drill core samples

MARKED	%	%	%						
	Cu	Pb	Zn						
9444	0.08	0.04	0.22						
9445	0.13	0.05	0.45						
9449	0.02	0.01	0.71						
9451	0.14	0.04	1.54						
9452	0.02	0.01	0.54						
9453	0.05	0.01	0.79						
9454 457	0.07	0.01	1.30						
9455	0.05	0.01	0.71						
9456	0.23	<0.01	5.28						
9457	0.04	<0.01	0.57						
9458	0.14	0.01	4.40						

Ag results to follow.

NOTE:

Rejects retained two weeks
Pulps retained three months
unless otherwise arranged

To: Bondar-Clegg & Company Ltd.

REPORT No A24 - 766

PAGE No. 1

BONDAR-CLEGG & COMPANY LTD.

DATE: October 9, 1974

136B Industrial Road
Whitehorse, Yukon


CERTIFICATE OF ASSAY

Samples submitted: Sept. 30, 1974
Results completed: Oct. 9, 1974

I hereby certify that the following are the results of assays made by us upon the herein described pulp samples.

MARKED	GOLD		SILVER								TOTAL VALUE PER TON (2000 LBS.)
	Ounces per Ton	Value per Ton	Ounces per Ton	Percent	Percent	Percent	Percent	Percent	Percent	Percent	
9329			1.6								
EB 93			6.6								
9335			0.27								
9336			0.29								
9337			0.04								
9343			0.12								
9344			0.85								
9345			0.42								
9346			0.06								
9347			4.9								
9348			trace								
9349			0.35								
9350			1.6								
9351			0.37								
9352			0.18								
9353			0.32								
9354			0.38								
9355			0.25								
9356			0.24								
9357			0.35								
9358			0.02								
9359			0.02								
9360			0.02								
9361			0.02								
9362			0.67								
9376			0.77								
9377			0.28								

cc Cyprus Anvil Mining Corp. - Vancouver


Registered Assayer, Province of British Columbia

To: Cyprus Anvil Mining

REPORT No A24 - 791B

PAGE No. 1

BONDAR-CLEGG & COMPANY LTD.

DATE: October 11, 1974

804 - 1550 Alberni Street
Vancouver, B. C.
ATTN: MR. G. SIMPSON


CERTIFICATE OF ASSAY

Samples submitted: Oct. 7, 1974
Results completed: October 11, 1974

I hereby certify that the following are the results of assays made by us upon the herein described pulp samples.

MARKED	GOLD		SILVER								TOTAL VALUE PER TON (2000 LBS.)
	Ounces per Ton	Value per Ton	Ounces per Ton	Percent	Percent	Percent	Percent	Percent	Percent		
9383			0.02								
9384			0.44								
9385			0.06								
9386			0.08								
9387			2.0								
9388			0.68								
9394			0.04								
9395			1.0								
9397			0.95								
9400			0.10								
EB-96			1.6								
9398			0.31								
9403			trace								
9404			0.31								
9405			7.0								
9406			7.4								
9407			1.5								
9408			0.96								
9410			1.1								
9411			0.25								
9415			2.1								
9417			0.16								
9418			0.04								
9419			1.1								
9422			0.19								

✓


Registered Assayer, Province of British Columbia

To: Cyprus Anvil Mining

REPORT No A24 - 791B

PAGE No. 1

BONDAR-CLEGG & COMPANY LTD.

DATE: October 11, 1974


804 - 1550 Alberni Street
Vancouver, B. C.
ATTN: MR. G. SIMPSON

CERTIFICATE OF ASSAY

Samples submitted: Oct. 7, 1974
Results completed: October 11, 1974

I hereby certify that the following are the results of assays made by us upon the herein described pulp samples.

MARKED	GOLD		SILVER								TOTAL VALUE PER TON (2000 LBS.)
	Ounces per Ton	Value per Ton	Ounces per Ton	Percent	Percent	Percent	Percent	Percent	Percent		
9383			0.02								
9384			0.44								
9385			0.06								
9386			0.08								
9387			2.0								
9388			0.68								
9394			0.04								
9395			1.0								
9397			0.95								
9400			0.10								
EB-96			1.6								
9398			0.31								
9403			trace								
9404			0.31								
9405			7.0								
9406			7.4								
9407			1.5								
9408			0.96								
9410			1.1								
9411			0.25								
9415			2.1								
9417			0.16								
9418			0.04								
9419			1.1								
9422			0.09								


Registered Assayer, Province of British Columbia

To: Cyprus Anvil Mining

REPORT No A24 - 791B

PAGE No. 1

BONDAR-CLEGG & COMPANY LTD.

DATE: October 11, 1974

804 - 1550 Alberni Street
Vancouver, B. C.
ATTN: MR. G. SIMPSON

CERTIFICATE OF ASSAY

Samples submitted: Oct. 7, 1974
Results completed: October 11, 1974

I hereby certify that the following are the results of assays made by us upon the herein described pulp samples.

MARKED	GOLD		SILVER								TOTAL VALUE PER TON (2000 LBS.)
	Ounces per Ton	Value per Ton	Ounces per Ton	Percent	Percent	Percent	Percent	Percent	Percent	Percent	
9383			0.02								
9384			0.44								
9385			0.06								
9386			0.08								
9387			2.0								
9388			0.68								
9394			0.04								
9395			1.0								
9397			0.95								
9400			0.10								
EB-96			1.6								
9398			0.31								
9403			trace								
9404			0.31								
9405			7.0								
9406			7.4								
9407			1.5								
9408			0.96								
9410			1.1								
9411			0.25								
9415			2.1								
9417			0.16								
9418			0.04								
9419			1.1								
9422			0.79								


 Registered Assayer, Province of British Columbia



BONDAR-CLEGG & COMPANY LTD.

geochemists • assayers • analytical chemists

1500 PEMBERTON AVENUE, NORTH VANCOUVER, B.C.
PHONE: 988-5315 TELEX: 04-54554

CERTIFICATE OF ASSAY

TO Cyprus Anvil Mining
804 - 1550 Alberni Street
Vancouver, B.C. V6G 1A5 ATTN: MR. G. SIMPSON

Report No: A24 - 806
October 17, 1974

I hereby certify that the following are the results of assays made by us upon the herein described pulp samples.

Table with 6 columns: MARKED, Ag Percent oz/ton, MARKED, Ag Percent oz/ton, MARKED, Percent. Rows include sample numbers 9391-9451 and their corresponding assay results.

NOTE:
Rejects retained two weeks
Pulps retained three months
unless otherwise arranged.

Registered Assayer/Province of British Columbia (with signature)



BONDAR-CLEGG & COMPANY LTD.

geochemists • assayers • analytical chemists

1500 PEMBERTON AVENUE, NORTH VANCOUVER, B.C.
PHONE: 988-5315 TELEEX: 04-54554

CERTIFICATE OF ASSAY

TO Cyprus Anvil Mining
804 - 1550 Alberni Street
Vancouver, B.C. V6G 1A5 ATTN: MR. G. SIMPSON

Report No: A24 - 806

October 17, 1974

I hereby certify that the following are the results of assays made by us upon the herein described pulp samples.

MARKED	Ag Percent oz/ton	MARKED	Ag Percent oz/ton	MARKED	Percent
9391	0.17	9452	0.04		
9392	0.56	9453	trace		
9393	0.32	9454	trace		
9399	0.22	9455	0.06		
9401	0.04	9456	trace		
9409	0.21	9457	trace		
9412	0.40	9458	0.08		
9414	0.20				
9416	0.36				
9428	0.81				
9430	1.1				
9432	0.61				
9434	0.41				
9435	0.63				
9439	1.3				
9440	3.1				
9441	0.67				
9444	0.41				
9445	0.36				
9449	0.06				
9451	trace				

NOTE:
Rejects retained two weeks
Pulps retained three months
unless otherwise arranged.

Registered Assayer, Province of British Columbia

**BONDAR-CLEGG & COMPANY LTD.**

geochemists • assayers • analytical chemists

1500 PEMBERTON AVENUE, NORTH VANCOUVER, B.C.

PHONE: 988-5315

TELEX: 04-54554

CERTIFICATE OF ASSAYTO Cyprus Anvil Mining

Report No: A24 - 806

804 - 1550 Alberni Street


October 17, 1974

Vancouver, B.C. V6G 1A5 ATTN: MR. G. SIMPSON**I hereby certify** that the following are the results of assays made by us upon the herein described pulp samples.

MARKED	Ag Percent oz/ton	MARKED	Ag Percent oz/ton	MARKED	Percent
9391	0.17	9452	0.04		
9392	0.56	9453	trace		
9393	0.32	9454	trace		
9399	0.22	9455	0.06		
9401	0.04	9456	trace		
9409	0.21	9457	trace		
9412	0.40	9458	0.08		
9414	0.20				
9416	0.36				
9428	0.81				
9430	1.1				
9432	0.61				
9434	0.41				
9435	0.63				
9439	1.3				
9440	3.1				
9441	0.67				
9444	0.41				
9445	0.36				
9449	0.06				
9451	trace				

NOTE:

Rejects retained two weeks
Pulps retained three months
unless otherwise arranged.


Registered Assayer, Province of British Columbia

To: Cyprus Anvil Ltd.

REPORT No A24 - 880

PAGE No. 1

BONDAR-CLEGG & COMPANY LTD.

DATE: November 7, 1974

555 South Flower Street
Los Angeles, California
90071

CERTIFICATE OF ASSAY

Samples Submitted: Nov. 5, 1974
Results completed: Nov. 7, 1974

Attention: Mr. G. Simpson

Should be no charge on these, less 14.00 per ton.

I hereby certify that the following are the results of assays made by us upon the herein described pulp samples.

MARKED	GOLD		SILVER								TOTAL VALUE PER TON (2000 LBS.)
	Ounces per Ton	Value per Ton	Ounces per Ton	Percent	Percent	Percent	Percent	Percent	Percent	Percent	
9326			0.18								
9327			0.25								
9328			0.04								
9330			0.10								
9331			0.61								
9332			0.33								
9333			0.17								
9334			0.18								

RECEIVED
NOV 12 1974
RECEIVED

[Signature]
Registered Assayer, Province of British Columbia

To: Cyprus Anvil Ltd.

REPORT No A24 - 880

PAGE No. 1

BONDAR-CLEGG & COMPANY LTD.

DATE: November 7, 1974

555 South Flower Street
Los Angeles, California
90071


CERTIFICATE OF ASSAY

Samples Submitted: **Nov. 5, 1974**
Results completed: **Nov. 7, 1974**

Attention: **Mr. G. Simpson**

I hereby certify that the following are the results of assays made by us upon the herein described pulp samples.

MARKED	GOLD		SILVER								TOTAL VALUE PER TON (2000 LBS.)
	Ounces per Ton	Value per Ton	Ounces per Ton	Percent	Percent	Percent	Percent	Percent	Percent		
9326			0.18								
9327			0.25								
9328			0.04								
9330			0.10								
9331			0.61								
9332			0.33								
9333			0.17								
9334			0.18								



[Handwritten Signature]
 Registered Assayer, Province of British Columbia

To: Cyprus Avvil Ltd.

REPORT No A24 - 880

PAGE No. 1

BONDAR-CLEGG & COMPANY LTD.

DATE: November 7, 1974

555 South Flower Street
Los Angeles, California
90071

CERTIFICATE OF ASSAY


Samples Submitted: Nov. 5, 1974
Results completed: Nov. 7, 1974

Attention: Mr. G. Simpson

I hereby certify that the following are the results of assays made by us upon the herein described pulp samples.

MARKED	GOLD		SILVER								TOTAL VALUE PER TON (2000 LBS.)
	Ounces per Ton	Value per Ton	Ounces per Ton	Percent	Percent	Percent	Percent	Percent	Percent	Percent	
9326			0.18								
9327			0.25								
9328			0.04								
9330			0.10								
9331			0.61								
9332			0.33								
9333			0.17								
9334			0.18								

RECEIVED
NOV 12 1974
REGISTERED


Registered Assayer, Province of British Columbia

804 - 1550 Alberni Street
 Vancouver, B.C. V6G 1A5

CERTIFICATE OF ASSAY

Samples submitted: Nov. 14/74
 Results completed: Nov. 21/74

I hereby certify that the following are the results of assays made by us upon the herein described pulp samples.

MARKED	GOLD		SILVER	Cu	Pb	Zn				TOTAL VALUE PER TON (2000 LBS.)
	Ounces per Ton	Value per Ton	Ounces per Ton	Percent	Percent	Percent	Percent	Percent	Percent	
9368			3.3	0.54	0.35	2.10				
9369			0.82	0.12	0.15	0.70				
9370			0.06	0.09	0.10	0.15				
9375			0.37	0.15	0.10	0.10				
9378			1.6	0.05	0.30	0.40				
9381			3.8	0.10	0.60	1.15				
9421			0.32	0.12	0.10	0.65				
9424			0.63	0.09	0.10	0.40				
9426			0.61	0.12	0.10	0.30				
9443			0.18	0.12	0.05	1.05				
9446			0.16	0.06	0.05	0.35				

✓ ✓ ✓ ✓


 Registered Assayer, Province of British Columbia

804 - 1550 Alberni Street
Vancouver, B.C. V6G 1A5

CERTIFICATE OF ASSAY

Samples submitted: Nov. 14/74
Results completed: Nov. 21/74I hereby certify that the following are the results of assays made by us upon the herein described pulp samples.

MARKED	GOLD		SILVER	Cu	Pb	Zn					TOTAL VALUE PER TON (2000 LBS.)
	Ounces per Ton	Value per Ton	Ounces per Ton	Percent	Percent	Percent	Percent	Percent	Percent	Percent	
9368			3.3	0.54	0.35	2.10					
9369			0.82	0.12	0.15	0.70					
9370			0.06	0.09	0.10	0.15					
9375			0.37	0.15	0.10	0.10					
9378			1.6	0.05	0.30	0.40					
9381			3.8	0.10	0.60	1.15					
9421			0.32	0.12	0.10	0.65					
9424			0.63	0.09	0.10	0.40					
9426			0.61	0.12	0.10	0.30					
9443			0.18	0.12	0.05	1.05					
9446			0.16	0.06	0.05	0.35					


804 - 1550 Alberni Street
Vancouver, B. C. V6G 1A5

CERTIFICATE OF ASSAY

Samples submitted: Nov. 14/74
Results completed: Nov. 21/74

I hereby certify that the following are the results of assays made by us upon the herein described pulp samples.

MARKED	GOLD		SILVER	Cu	Pb	Zn					TOTAL VALUE PER TON (2000 LBS.)
	Ounces per Ton	Value per Ton	Ounces per Ton	Percent	Percent	Percent	Percent	Percent	Percent		
9368			3.3	0.54	0.35	2.10					
9369			0.82	0.12	0.15	0.70					
9370			0.06	0.09	0.10	0.15					
9375			0.37	0.15	0.10	0.10					
9378			1.6	0.05	0.30	0.40					
9381			3.8	0.10	0.60	1.15					
9421			0.32	0.12	0.10	0.65					
9424			0.63	0.09	0.10	0.40					
9426			0.61	0.12	0.10	0.30					
9443			0.18	0.12	0.05	1.05					
9446			0.16	0.06	0.05	0.35					


 Registered Assayer, Province of British Columbia



BONDAR-CLEGG & COMPANY LTD.

1500 PEMBERTON AVE., NORTH VANCOUVER, B.C. PHONE: 985-0681 TELEX: 04-54554

Geochemical Lab Report

Extraction Hot Aqua Regia

Report No. 24 - 849

PROJECT: W.O.466

P. O. 40634

Method Atomic Absorption

From Cyprus Anvil Mining Corp.

Fraction Used -100 mesh

Date November 12 1974

SAMPLE NO.	Cu ppm	Pb ppm	Zn ppm	Ag ppm	SAMPLE NO.	Cu ppm	Pb ppm	Zn ppm	Ag ppm
9338	82	230	400	3.8	9424 ✓	890	950	3800	8.1
9340	195	860	540	7.0	9425	450	500	1220	8.2
9341	115	330	440	4.9	9426 ✓	1280	1110	2950	13.5
9342	187	700	500	8.5	9427	180	300	350	7.0
9363	153	1700	1460	5.3	9429	370	133	480	4.7
9364	330	960	370	7.0	9431	280	158	670	4.8
9365	355	820	520	8.8	9433	460	98	1270	5.0
9366	186	178	195	2.8	9436 ?	280	60	255	2.4
9367	670	680	350	11.2	9437	810	410	460	5.2
9368 ✓	6200	3300	16200	31.0	9438	570	400	340	7.0
9369 ✓	1260	1350	6200	8.9	³ 9439 ?	880	2900	1220	4.5
9370 ✓	1050	400	1300	8.0	9442	680	200	460	5.0
9371	230	65	320	3.0	9443 ✓	1200	220	10000	9.2
9372	80	20	92	1.5	9446 ✓	580	230	3350	7.6
9373	150	24	47	1.4	9447	150	78	132	2.0
9374	320	57	300	2.6	9448	130	190	990	4.7
9375 ✓	1510	480	660	13.8	9450	160	18	440	1.7
9378 ✓	520	2900	3900	6.6	9459	196	26	460	1.9
9379	166	2000	1300	9.0					
9380	265	800	350	5.8					
9381 ✓	1020	6000	9600	95.0 ✓					
9382	290	200	3200	7.0	NOTE: Ag values not corrected for possible background effect.				
9389	440	410	3500	6.6					
9390	410	810	2700	12.0					
9396	167	64	620	2.4					
9402 ?	190	36	820	2.0					
9413	230	600	245	9.0					
9420	290	700	800	5.7					
9421 ✓	1180	880	5900	13.0					
9423	375	390	640	8.0					



BONDAR-CLEGG & COMPANY LTD.

1500 PEMBERTON AVE., NORTH VANCOUVER, B.C. PHONE: 985-0681 TELEX: 04-54554

Geochemical Lab Report

Extraction Hot Aqua Regia

Report No. 24 - 849 PROJECT: W.O.466
P. O. 40634


Method Atomic Absorption

From Cyprus Anvil Mining Corp.

Fraction Used -100 mesh

Date November 12 74

SAMPLE NO.	Cu ppm	Pb ppm	Zn ppm	Ag ppm	SAMPLE NO.	Cu ppm	Pb ppm	Zn ppm	Ag ppm
9338	82	230	400	3.8	9424	890	950	3800	8.1
9340	195	860	540	7.0	9425	450	500	1220	8.2
9341	115	330	440	4.9	9426	1280	1110	2950	13.5
9342	187	700	500	8.5	9427	180	300	350	7.0
9363	153	1700	1460	5.3	9429	370	133	480	4.7
9364	330	960	370	7.0	9431	280	158	670	4.8
9365	355	820	520	8.8	9433	460	98	1270	5.0
9366	186	178	195	2.8	9436	280	60	255	2.4
9367	670	680	350	11.2	9437	810	410	460	5.2
9368	6200	3300	16200	31.0	9438	570	400	340	7.0
9369	1260	1350	6200	8.9	9439	880	2900	1220	4.5
9370	1050	400	1300	8.0	9442	680	200	460	5.0
9371	230	65	320	3.0	9443	1200	220	10000	9.2
9372	80	20	92	1.5	9446	580	230	3350	7.6
9373	150	24	47	1.4	9447	150	78	132	2.0
9374	320	57	300	2.6	9448	130	190	990	4.7
9375	1510	480	660	13.8	9450	160	18	440	1.7
9378	520	2900	3900	6.6	9459	196	26	460	1.9
9379	166	2000	1300	9.0					
9380	265	800	350	5.8					
9381	1020	6000	9600	95.0					
9382	290	200	3200	7.0	NOTE: Ag values not corrected for possible background effect.				
9389	440	410	3500	6.6					
9390	410	810	2700	12.0					
9396	167	64	620	2.4					
9402	190	36	820	2.0					
9413	230	600	245	9.0					
9420	290	700	800	5.7					
9421	1180	880	5900	13.0					
9423	375	390	640	8.0					



BONDAR-CLEGG & COMPANY LTD.

1500 PEMBERTON AVE., NORTH VANCOUVER, B.C. PHONE: 985-0681 TELEX: 04-54554

Geochemical Lab Report

Extraction Hot Aqua Regia

Report No. 24 - 849 PROJECT: W.O.466
P. O. 40634

Method Atomic Absorption

From Cyprus Anvil Mining Corp.

Fraction Used -100 mesh

Date November 12 1974

SAMPLE NO.	Cu ppm	Pb ppm	Zn ppm	Ag ppm	SAMPLE NO.	Cu ppm	Pb ppm	Zn ppm	Ag ppm
9338	82	230	400	3.8	9424	890	950	3800	8.1
9340	195	860	540	7.0	9425	450	500	1220	8.2
9341	115	330	440	4.9	9426	1280	1110	2950	13.5
9342	187	700	500	8.5	9427	180	300	350	7.0
9363	153	1700	1460	5.3	9429	370	133	480	4.7
9364	330	960	370	7.0	9431	280	158	670	4.8
9365	355	820	520	8.8	9433	460	98	1270	5.0
9366	186	178	195	2.8	9436	280	60	255	2.4
9367	670	680	350	11.2	9437	810	410	460	5.2
9368	6200	3300	16200	31.0	9438	570	400	340	7.0
9369	1260	1350	6200	8.9	9439	880	2900	1220	4.5
9370	1050	400	1300	8.0	9442	680	200	460	5.0
9371	230	65	320	3.0	9443	1200	220	10000	9.2
9372	80	20	92	1.5	9446	580	230	3350	7.6
9373	150	24	47	1.4	9447	150	78	132	2.0
9374	320	57	300	2.6	9448	130	190	990	4.7
9375	1510	480	660	13.8	9450	160	18	440	1.7
9378	520	2900	3900	6.6	9459	196	26	460	1.9
9379	166	2000	1300	9.0					
9380	265	800	350	5.8					
9381	1020	6000	9600	95.0					
9382	290	200	3200	7.0	NOTE: Ag values not corrected for possible background effect.				
9389	440	410	3500	6.6					
9390	410	810	2700	12.0					
9396	167	64	620	2.4					
9402	190	36	820	2.0					
9413	230	600	245	9.0					
9420	290	700	800	5.7					
9421	1180	880	5900	13.0					
9423	375	390	640	8.0					

DDH #2

						Cu	Pb	Zn	Ag
8-13	9405	x	mg-hg	5'		0.72	1.55	4.00	
13-18	9406	x	mg-hg	5'		0.32	2.60	4.80	
18-28	9407	x	lg-mg	10'		0.08	0.63	0.81	
28-38	9408	x	lg	10'		0.10	0.75	0.81	
38-46	9409		vlg	8'		0.03	0.05	0.49	
46-56	9410		lg-mg	10'		0.08	0.17	1.30	
56-66	9411		lg-mg	10'		0.10	0.06	0.86	
66-74	9412		lg	8'		0.03	0.12	0.19	
74-84	9413		vlg-b	10'					
84-94	9414		vlg-b	10'		0.05	0.20	0.12	
94-103 1/2	9415	x	lg-mg	9 1/2'		0.31	2.60	2.34	
103 1/2-111 1/2	9416		lg	8'		0.12	0.27	0.33	
111 1/2-125 1/2	9417	x	lg	14'		0.07	0.06	1.30	
125 1/2-133	9418	x	lg	7 1/2'		0.06	0.06	0.79	
133-140	9419	x	mg	7'	7'	0.73	0.26	4.56	
140-154	9393		lg	14'	14'	0.04	0.09	0.11	
154-163	9394	x	mg	9'		0.06	0.11	1.40	
163-169	9395	x	mg	6'	15'	0.29	0.27	3.16	
169-174 1/2	9396		vlg	5 1/2'	5 1/2'				
174 1/2-179	9397	x	mg	4 1/2'	4 1/2'	0.20	0.24	1.92	
179-185	9398	x	vlg	6'		0.05	0.07	0.17	
185-200	9399		vlg	15'	21'	0.02	0.06	0.24	
200-207	9400	x	mg	7'	7'		0.08	0.04	2.60
207-217	9401		vlg-b	10'			0.01	0.01	0.05
217-227	9402		vlg-b	10'	29'				
227-236	9403	x	mg-lg	9'			0.04	0.01	0.88
236-241	9404	x	mg	5'	5'		0.06	0.08	1.56
241-247	9382	x	vlg-lg	6'	6'				
247-254	9383	x		7'		0.16	0.02	2.48	
254-261	9384	x	hg-mg	7'	14'	0.18	0.08	2.68	
261-269	9385		lg	8'	22'	0.06	0.02	0.72	
269-283	9386	x	vlg	14'		0.04	0.06	0.19	
283-288	9387	x		5'		0.15	2.60	2.72	
288-294	9388	x	mg	6'	11'	0.13	0.54	1.76	
294-304	9389		lg	10'					
304-314	9390		vlg-lg	10'					
314-324	9391		vlg-b	10'		0.02	0.05	0.05	
324-334	9392		vlg-lg	10'		0.05	0.18	0.13	
334-358	9447		b	24'					

best sect
133-294
including
65 1/2' of
mg grade
it is or
less com
mostly
Zn

DDH #2 (cont.)

				Cu	Pb	Zn	Ag
358-368	9420	10'	vlg				
369-377	9421	9'	vlg				
377-383	9422	X 6'	lg	0.09	0.05	1.80	
383-393	9423	10'	vlg				
393-403	9424	10'	vlg				
403-410	9425	7'	vlg				
410-420	9426	10'	lg				
420-432	9427	12'	vlg				
432-443	9428	11'	lg	0.16	0.15	2.04	
443-463	9429	20'	b				
463-474	9430	11'	mg	0.26	0.47	1.88	
474-486	9431	12'	vlg-b				
486-495	9432	9'	lg	0.11	0.11	0.61	
495-505	9433	10'	b				
505-515	9434	10'	lg	0.19	0.03	0.64	
515-525	9435	10' 10' mg		0.31	0.05	1.09	
525-535	9446	10'	vlg				
535-542	9445	7'	lg-mg	0.13	0.05	0.45	
542-551	9444	9'	lg	0.08	0.04	0.22	
551-566	9443	15'	lg				
566-578	9442	12'	b				
578-592	9441	14'	b	0.30	0.07	0.24	
592-597	9440	5'	mg-hg	1.72	0.16	4.64	
597-609	9439	12'	vlg	0.68	0.14	0.87	
609-618	9438	9'	b				
618-635	9437	17'	lg				
635-658	9436	23'	b				

DDH

D-74-1

			CU	Pb	Zn	Ag
32-40	9326	2'	0.45	0.08	2.76	(0.864)
40-50	9327	10'	0.15	0.17	0.26	(0.874)
50-60	9328	10'	0.06	0.11	0.99	(0.548)
60-70	9329	10'	0.09	0.46	0.82	(2.29)
70-80	9330	10'	0.05	0.06	0.06	(0.368)
80-90	9331	10'	0.11	0.31	0.14	(1.04)
90-100	9332	10'	0.36	0.05	1.20	(0.654)
100-110	9333	10'	0.25	0.02	2.32	(0.542)
110-120	9334	10'	0.11	0.05	0.79	(0.397)
120-130	9335	10'	0.06	0.13	0.40	0.27
130-140	9336	10'	0.10	0.11	0.79	0.27
140-150	9337	10'	< 0.01	0.02	0.05	0.04
150-160	9338	10'				
160-170	9339	10'				
170-180	9340	10'				
180-190	9341	10'				
190-200	9342	10'				
200-210	9343	10'	< 0.01	0.03	0.03	0.12
210-220	9344	10'	0.09	0.54	1.44	0.85
220-230	9345	10'	0.07	0.15	0.68	0.42
230-240	9346	10'	0.02	0.07	0.42	0.06
240-250	9347	10'	0.37	1.38	1.08	4.96
250-260	9348	10'	0.04	0.03	0.05	Tr
260-270	9349	10'	0.03	0.13	0.05	0.35
270-280	9350	10'	0.23	0.68	0.80	1.60
280-290	9351	10'	0.18	0.07	2.20	0.37
290-300	9352	10'	0.08	0.05	0.50	0.18
300-310	9353	10'	0.03	0.04	0.05	0.32
310-320	9354	10'	0.03	0.12	0.07	0.38
320-330	9355	10'	0.03	0.05	0.40	0.25
330-340	9356	10'	0.07	0.04	1.05	0.24
340-350	9357	10'	0.05	0.08	0.29	0.35
350-360	9358	10'	0.06	0.16	0.30	0.02
360-370	9359	10'	0.10	0.06	0.25	0.02
370-380	9360	10'	0.22	0.05	4.20	0.02
380-390	9361	10'	0.03	0.05	0.13	0.02
390-400	9362	10'	0.11	0.30	1.10	0.67

DDH - 0-74-1 (cont)

Cu

Pb

Zn

Ag

400 - 410	9363				
410 - 420	9364				
420 - 430	9365				
430 - 440	9366				
440 - 450	9367				
450 - 460	9368				
460 - 470	9369				
470 - 480	9370				
480 - 490	9371				
490 - 500	9372				
500 - 510	9373				
510 - 520	9374				
520 - 530	9375				
530 - 540	9376	0.30	0.20	0.99	0.77
540 - 550	9377	0.06	0.10	0.21	0.28
550 - 560	9378				
560 - 570	9379				
570 - 580	9380				
580 - 590	9381				

22 more

DOH 0-74-3.

				Cu	Pb	Zn	Ag
110 - 130	9448	20'	vlg-b				
130 - 138	9449	8'	lg	0.02	0.01	0.71	
138 - 150	9450	12'	vlg-b				
150 - 155	9451	5'	lg-mg	0.14	0.04	1.54	
155 - 165 $\frac{1}{2}$	9452	10 $\frac{1}{2}$ '	vlg	0.02	0.01	0.54	
165 $\frac{1}{2}$ - 173	9453	7 $\frac{1}{2}$ '	lg	0.05	0.01	1.12 0.79	
173 - 179 $\frac{1}{2}$	9454	6 $\frac{1}{2}$ '	lg	0.07	0.01	1.30	
179 $\frac{1}{2}$ - 183 $\frac{1}{2}$	9455	4'	b	0.05	0.01	0.71	
183 $\frac{1}{2}$ - 187 $\frac{1}{2}$	9456	4'	-mg	0.23	<0.01	5.28	
187 $\frac{1}{2}$ - 193	9457	5 $\frac{1}{2}$ '	vlg	0.04	0.01	0.57	
193 - 196	9458	6'	mg	3.04	0.01	4.40	
196 - 203	9459	7'	b				