

```
*****
*
*   C Y P R U S   A N V I L   M I N I N G   C O R P O R A T I O N   *
*
*****
*
*               SYSTEM = DDHDB
*             PROGRAM = DH023
*
*           FRI, MAR  6, 1987,  1:13 PM
*
*****
*
*   REPORTING OF 'SECTION-MASTER' DATA SETS
*   FOR THE CURRENT 'DDHDB' DATA BASE.
*
*****
```

017394

'PROPERTY-MASTER' DATA SET ITEM VALUES

PROPERTY-NAME = '!THE IMPERIAL ANVIL!'

UTM-LIMITS = .000 NORTHING (MIN)
 .000 (MAX)
 .000 EASTING (MIN)
 .000 (MAX)

UTM-ZONE = 0

TRUE-NORTH TO UTM-NORTH ANGLE = .000000

	----- GRID ORIGIN -----		--- SCALE FACTORS ---	
	NORTHING	EASTING	ELEVATION	ANGLE
				HORIZONTAL
				VERTICAL
GEOLOGICAL GRID =	.000	.000	.000	.000000 .00000000 .00000000 0
MINE MODEL GRID =	.000	.000	.000	.000000 1.00000000 1.00000000 1
MINE SURVEY GRID =	.000	.000	.000	.000000 1.00000000 1.00000000 1

90 CROSS-SECTIONS FOUND FOR IN 'DDHDB' = !THE IMPERIAL ANVIL!

CROSS-SECTION DATA STORED FOR 'DDHDB' = !THE IMPERIAL ANVIL!

SECTION NAME	COORDINATE SYSTEM	----- POINT-1 ----- NORTHING EASTING	----- POINT-2 ----- NORTHING EASTING	- ELEVATIONS - UPPER LOWER	- PLOT RATIO - HORIZ. VERT.	VIEW AZIMUTH (DEGREES)	STRUCTURE PLUNGE TREND
09+000	UTM	8250.0 12650.0	6000.0 15000.0	4400.0 2900.0	600.0 600.0 FEET FEET	43.75	0 0
10+000	UTM	8350.0 12750.0	6100.0 15100.0	4400.0 2900.0	600.0 600.0 FEET FEET	43.75	0 0
11+000	UTM	8450.0 12850.0	6200.0 15200.0	4400.0 2900.0	600.0 600.0 FEET FEET	43.75	0 0
116+000	UTM	7600.0 12400.0	10600.0 15400.0	4400.0 2900.0	600.0 600.0 FEET FEET	315.00	0 0
116+070	UTM	7550.0 12450.0	10550.0 15450.0	4400.0 2900.0	600.0 600.0 FEET FEET	315.00	0 0
117+000	UTM	7500.0 12500.0	10500.0 15500.0	4400.0 2900.0	600.0 600.0 FEET FEET	315.00	0 0
117+070	UTM	6950.5 12049.5	10450.5 15549.5	4400.0 2900.0	600.0 600.0 FEET FEET	315.00	0 0
118+000	UTM	7400.0 12600.0	10400.0 15600.0	4400.0 2900.0	600.0 600.0 FEET FEET	315.00	0 0
118+070	UTM	7350.0 12650.0	10350.0 15650.0	4400.0 2900.0	600.0 600.0 FEET FEET	315.00	0 0
119+000	UTM	7300.0 12700.0	10300.0 15700.0	4400.0 2900.0	600.0 600.0 FEET FEET	315.00	0 0
119+070	UTM	7250.0 12750.0	10250.0 15750.0	4400.0 2900.0	600.0 600.0 FEET FEET	315.00	0 0
12+000	UTM	8550.0 12950.0	6300.0 15300.0	4400.0 2900.0	600.0 600.0 FEET FEET	43.75	0 0
120+000	UTM	7200.0 12800.0	10200.0 15800.0	4400.0 2900.0	600.0 600.0 FEET FEET	315.00	0 0
120+070	UTM	7150.0 12850.0	10150.0 15850.0	4400.0 2900.0	600.0 600.0 FEET FEET	315.00	0 0
121+000	UTM	7100.0 12900.0	10100.0 15900.0	4400.0 2900.0	600.0 600.0 FEET FEET	315.00	0 0
121+070	UTM	7050.0 12950.0	10050.0 15950.0	4400.0 2900.0	600.0 600.0 FEET FEET	315.00	0 0
122+000	UTM	7000.0 13000.0	10000.0 16000.0	4400.0 2900.0	600.0 600.0 FEET FEET	315.00	0 0

122+020	UTM	6985.9	13014.1	9985.9	16014.1	4400.0	2900.0	600.0 FEET	600.0 FEET	315.00	0	0
122+070	UTM	6950.0	13050.0	9950.0	16050.0	4400.0	2900.0	600.0 FEET	600.0 FEET	315.00	0	0
123+000	UTM	6900.0	13100.0	9900.0	16100.0	4400.0	2900.0	600.0 FEET	600.0 FEET	315.00	0	0

CROSS-SECTION DATA STORED FOR 'DDHDB' = !THE IMPERIAL ANVIL!

SECTION NAME *****	COORDINATE SYSTEM	---- POINT-1 ---- NORTHING EASTING	---- POINT-2 ---- NORTHING EASTING	- ELEVATIONS - UPPER LOWER	- PLOT RATIO - HORIZ. VERT.	VIEW AZIMUTH (DEGREES)	STRUCTURE PLUNGE TREND
123+015	UTM	6889.7 13110.3	9889.7 16110.3	4400.0 2900.0	600.0 600.0 FEET FEET	315.00	0 0
123+070	UTM	6850.0 13150.0	9850.0 16150.0	4400.0 2900.0	600.0 600.0 FEET FEET	315.00	0 0
124+000	UTM	6800.0 13200.0	9550.0 15950.0	4400.0 2900.0	600.0 600.0 FEET FEET	315.00	0 0
124+022	UTM	6784.4 13215.6	9534.4 15965.6	4400.0 2900.0	600.0 600.0 FEET FEET	315.00	0 0
124+070	UTM	6750.0 13250.0	9500.0 16000.0	4400.0 2900.0	600.0 600.0 FEET FEET	315.00	0 0
✓ 125+000	UTM	6700.0 13300.0	9450.0 16050.0	4400.0 2900.0	600.0 600.0 FEET FEET	315.00	0 0
125+070	UTM	6650.0 13350.0	9400.0 16100.0	4400.0 2900.0	600.0 600.0 FEET FEET	315.00	0 0
✓ 126+000	UTM	6600.0 13400.0	9350.0 16150.0	4400.0 2900.0	600.0 600.0 FEET FEET	315.00	0 0
126+023	UTM	6583.7 13416.3	9333.7 16166.3	4400.0 2900.0	600.0 600.0 FEET FEET	315.00	0 0
126+070	UTM	6550.0 13450.0	9300.0 16200.0	4400.0 2900.0	600.0 600.0 FEET FEET	315.00	0 0
✓ 127+000	UTM	6500.0 13500.0	9250.0 16250.0	4400.0 2900.0	600.0 600.0 FEET FEET	315.00	0 0
127+009	UTM	6493.6 13506.4	9243.6 16256.4	4400.0 2900.0	600.0 600.0 FEET FEET	315.00	0 0
127+070	UTM	6450.0 13550.0	9200.0 16300.0	4400.0 2900.0	600.0 600.0 FEET FEET	315.00	0 0
128+000	UTM	6400.0 13600.0	9150.0 16350.0	4400.0 2900.0	600.0 600.0 FEET FEET	315.00	0 0
128+020	UTM	6385.9 13614.1	9135.9 16364.1	4400.0 2900.0	600.0 600.0 FEET FEET	315.00	0 0
128+070	UTM	6350.0 13650.0	9100.0 16400.0	4400.0 2900.0	600.0 600.0 FEET FEET	315.00	0 0
129+000	UTM	6300.0 13700.0	9050.0 16450.0	4400.0 2900.0	600.0 600.0 FEET FEET	315.00	0 0

129+070	UTM	6250.0	13750.0	9000.0	16500.0	4400.0	2900.0	600.0 FEET	600.0 FEET	315.00	0	0
13+000	UTM	8650.0	13150.0	6400.0	15400.0	4400.0	2900.0	600.0 FEET	600.0 FEET	45.00	0	0
130+000	UTM	6200.0	13800.0	8950.0	16550.0	4400.0	2900.0	600.0 FEET	600.0 FEET	315.00	0	0

CROSS-SECTION DATA STORED FOR 'DDHDB' = !THE IMPERIAL ANVIL!

SECTION NAME	COORDINATE SYSTEM	---- POINT-1 ---- NORTHING EASTING	---- POINT-2 ---- NORTHING EASTING	- ELEVATIONS - UPPER LOWER	- PLOT RATIO - HORIZ. VERT.	VIEW AZIMUTH (DEGREES)	STRUCTURE PLUNGE TREND

130+070	UTM	6150.0 13850.0	8900.0 16600.0	4400.0 2900.0	600.0 600.0 FEET FEET	315.00	0 0
131+000	UTM	6100.0 13900.0	8850.0 16650.0	4400.0 2900.0	600.0 600.0 FEET FEET	315.00	0 0
131+022	UTM	6084.4 13915.6	8834.4 16665.6	4400.0 2900.0	600.0 600.0 FEET FEET	315.00	0 0
131+070	UTM	6050.0 13950.0	8800.0 16700.0	4400.0 2900.0	600.0 600.0 FEET FEET	315.00	0 0
132+000	UTM	6000.0 14000.0	8750.0 16750.0	4400.0 2900.0	600.0 600.0 FEET FEET	315.00	0 0
132+052	UTM	5963.2 14036.8	8713.2 16786.8	4400.0 2900.0	600.0 600.0 FEET FEET	315.00	0 0
132+070	UTM	5950.0 14050.0	8700.0 16800.0	4400.0 2900.0	600.0 600.0 FEET FEET	315.00	0 0
133+000	UTM	5900.0 14100.0	8650.0 16850.0	4400.0 2900.0	600.0 600.0 FEET FEET	315.00	0 0
133+070	UTM	5850.0 14150.0	8600.0 16900.0	4400.0 2900.0	600.0 600.0 FEET FEET	315.00	0 0
134+000	UTM	5800.0 14200.0	8550.0 16950.0	4400.0 2900.0	600.0 600.0 FEET FEET	315.00	0 0
134+047	UTM	5766.8 14233.2	8516.8 16983.2	4400.0 2900.0	600.0 600.0 FEET FEET	315.00	0 0
134+070	UTM	5750.0 14250.0	8500.0 17000.0	4400.0 2900.0	600.0 600.0 FEET FEET	315.00	0 0
135+000	UTM	5700.0 14300.0	8450.0 17050.0	4400.0 2900.0	600.0 600.0 FEET FEET	315.00	0 0
135+054	UTM	5661.8 14338.2	8411.8 17088.2	4400.0 2900.0	600.0 600.0 FEET FEET	315.00	0 0
135+122	UTM	5613.7 14386.3	8363.7 17136.3	4400.0 2900.0	600.0 600.0 FEET FEET	315.00	22 315
14+000	UTM	8650.0 13250.0	6500.0 15500.0	4400.0 2900.0	600.0 600.0 FEET FEET	43.70	19 225
14+100	UTM	9070.7 13070.7	6429.3 15712.1	4400.0 2900.0	600.0 600.0 FEET FEET	45.00	19 225

14+125	UTM	8838.4	13338.4	6588.4	15588.4	4400.0	2900.0	600.0 FEET	600.0 FEET	45.00	0	0
15+000	UTM	8850.0	13350.0	6600.0	15600.0	4400.0	2900.0	600.0 FEET	600.0 FEET	45.00	0	0
16+000	UTM	8950.0	13450.0	6700.0	15700.0	4400.0	2900.0	600.0 FEET	600.0 FEET	45.00	0	0

CROSS-SECTION DATA STORED FOR 'DDHDB' = !THE IMPERIAL ANVIL!

SECTION NAME	COORDINATE SYSTEM	---- POINT-1 ---- NORTHING EASTING	---- POINT-2 ---- NORTHING EASTING	- ELEVATIONS - UPPER LOWER	- PLOT RATIO - HORIZ. VERT.	VIEW AZIMUTH (DEGREES)	STRUCTURE PLUNGE TREND

17+000	UTM	9050.0 13550.0	6800.0 15800.0	4400.0 2900.0	600.0 600.0 FEET FEET	45.00	0 0
18+000	UTM	9150.0 13650.0	6900.0 15900.0	4400.0 2900.0	600.0 600.0 FEET FEET	45.00	0 0
19+000	UTM	9250.0 13750.0	7000.0 16000.0	4400.0 2900.0	600.0 600.0 FEET FEET	45.00	0 0
19+094	UTM	9316.5 13816.5	7066.5 16066.5	4400.0 2900.0	600.0 600.0 FEET FEET	45.00	0 0
20+000	UTM	9350.0 13850.0	7100.0 16100.0	4400.0 2900.0	600.0 600.0 FEET FEET	45.00	0 0
20+026	UTM	9368.4 13868.4	7118.4 16118.4	4400.0 2900.0	600.0 600.0 FEET FEET	45.00	0 0
21+000	UTM	9450.0 13950.0	7200.0 16200.0	4400.0 2900.0	600.0 600.0 FEET FEET	45.00	0 0
21+070	UTM	9749.5 13749.5	7249.5 16249.5	4400.0 2900.0	600.0 600.0 FEET FEET	45.00	0 0
22+000	UTM	9550.0 14050.0	7300.0 16300.0	4400.0 2900.0	600.0 600.0 FEET FEET	45.00	0 0
22+070	UTM	9849.8 13849.8	7349.8 16349.8	4400.0 2900.0	600.0 600.0 FEET FEET	45.00	0 0
23+000	UTM	9650.0 14150.0	7400.0 16400.0	4400.0 2900.0	600.0 600.0 FEET FEET	45.00	0 0
23+070	UTM	9949.5 13949.5	7449.5 16449.5	4400.0 2900.0	600.0 600.0 FEET FEET	45.00	0 0
24+000	UTM	9750.0 14250.0	7500.0 16500.0	4400.0 2900.0	600.0 600.0 FEET FEET	45.00	0 0
24+070	UTM	10049.5 14049.5	7549.5 16549.5	4400.0 2900.0	600.0 600.0 FEET FEET	45.00	0 0
24+200	UTM	10141.4 14141.4	7500.0 16782.8	4400.0 2900.0	600.0 600.0 FEET FEET	45.00	0 0
25+000	UTM	9850.0 14350.0	7600.0 16600.0	4400.0 2900.0	600.0 600.0 FEET FEET	45.00	0 0
25+070	UTM	10149.5 14149.5	7649.5 16649.5	4400.0 2900.0	600.0 600.0 FEET FEET	45.00	0 0

26+000	UTM	9950.0	14450.0	7700.0	16700.0	4400.0	2900.0	600.0 FEET	600.0 FEET	45.00	0	0
26+070	UTM	10249.5	14249.5	7749.5	16749.5	4400.0	2900.0	600.0 FEET	600.0 FEET	45.00	0	0
27+000	UTM	10050.0	14550.0	7800.0	16800.0	4400.0	2900.0	600.0 FEET	600.0 FEET	45.00	0	0

CROSS-SECTION DATA STORED FOR 'DDHDB' = !THE IMPERIAL ANVIL!

SECTION NAME	COORDINATE SYSTEM	----- POINT-1 ----- NORTHING EASTING	----- POINT-2 ----- NORTHING EASTING	- ELEVATIONS - UPPER LOWER	- PLOT RATIO - HORIZ. VERT.	VIEW AZIMUTH (DEGREES)	STRUCTURE PLUNGE TREND

27+070	UTM	10349.8 14349.8	7849.8 16849.8	4400.0 2900.0	600.0 600.0 FEET FEET	45.00	0 0
28+000	UTM	10150.0 14650.0	7900.0 16900.0	4400.0 2900.0	600.0 600.0 FEET FEET	45.00	0 0
28+070	UTM	10449.5 14449.5	7949.5 16949.5	4400.0 2900.0	600.0 600.0 FEET FEET	45.00	0 0
29+000	UTM	10250.0 14750.0	8000.0 17000.0	4400.0 2900.0	600.0 600.0 FEET FEET	45.00	0 0
30+000	UTM	10350.0 14850.0	8100.0 17100.0	4400.0 2900.0	600.0 600.0 FEET FEET	45.00	0 0
31+000	UTM	10450.0 14950.0	8200.0 17200.0	4400.0 2900.0	600.0 600.0 FEET FEET	45.00	0 0
32+000	UTM	10550.0 15050.0	8300.0 17300.0	4400.0 2900.0	600.0 600.0 FEET FEET	45.00	0 0
33+000	UTM	10650.0 15150.0	8400.0 17400.0	4400.0 2900.0	600.0 600.0 FEET FEET	45.00	0 0
4+500	UTM	8353.6 12353.6	5712.1 14995.0	4400.0 2900.0	600.0 600.0 FEET FEET	45.00	19 225
9+100	UTM	8570.7 12570.7	5929.3 15212.1	4400.0 2900.0	600.0 600.0 FEET FEET	45.00	19 225

DDH	UTM-N	UTM-E	UTM-ELEV	TOTAL DEPTH	SECTION	RFE	DIR	PLUNGE	ANGLE	DHD	SSC
*****	0.0	0.0	0.0	0.0							
✓65-53	6,605.4	14,741.4	4,019.8	427.0		S2	210			1	
✓65-55	7,035.3	15,525.7	4,009.4	233.0		S2	210			1	
✓65006	9,599.6	14,399.9	4,099.8	500.0						1	
✓65007	9,999.6	14,400.0	4,130.8	500.0						1	
✓65008	9,599.8	13,599.9	4,169.1	600.0						1	
✓65009	9,199.8	13,998.3	4,060.5	472.0						1	
✓65012	9,199.6	13,598.3	4,104.5	396.0						1	
✓65017	9,999.5	14,800.0	4,221.8	400.0						1	
✓66-03	9,200.0	14,398.0	4,100.4	744.0	118+000	S2	235			1	1
✓66-05	8,800.1	13,999.5	4,018.1	673.2	118+000	S2	235			1	1
✓66-06	9,599.5	14,800.0	4,188.3	766.0	118+000	S2	235			1	1
✓66-07	9,200.6	14,798.3	4,156.7	810.0	120+000	S2	235			1	1
✓66-10	8,790.5	14,795.4	4,121.4	849.0	122+020	S2	235			1	1
✓66-11	9,199.3	15,199.7	4,191.5	759.5	122+020	S2	235			1	1
✓66-46	9,398.9	14,599.9	4,161.1	800.0	118+000	S2	235			1	1
✓66-47	9,599.8	15,199.8	4,217.1	700.0	120+000	S2	235			1	1
✓66-49	8,799.3	14,399.5	4,059.5	750.0	120+000	S2	235			1	1
✓66-52	8,996.9	14,199.1	4,038.8	725.0	118+000	S2	235			1	1
✓66002	9,599.7	13,999.9	4,136.9	534.0						1	
✓66004	9,999.7	14,000.0	4,192.7	700.0						1	
✓66008	9,799.6	13,799.0	4,189.5	700.0						1	
✓66018	10,199.7	14,200.0	4,180.6	400.0						1	
✓66022	9,797.9	14,199.0	4,124.1	430.5						1	
✓66026	9,399.9	13,397.3	4,150.1	500.0						1	
✓66030	9,793.0	14,536.3	4,124.7	526.0						1	
✓66031	9,399.6	13,797.3	4,128.0	500.0						1	
✓66033	9,399.3	14,197.3	4,078.6	461.5						1	
✓66035	10,095.8	14,099.6	4,178.9	405.0						1	
✓66043	8,995.1	13,791.9	4,034.4	400.0						1	
✓66053	10,098.6	14,501.9	4,140.9	300.0						1	
✓66055	9,028.0	13,757.0	4,047.0	600.0						1	
✓66057	9,919.0	14,690.0	4,207.8	600.0						1	
✓66E-01	7,541.5	15,604.0	4,012.0	452.5	132	S2				1	
✓66E-02	7,389.8	15,825.1	4,009.0	423.0		S2	210			1	
✓66E-03	7,616.0	15,908.0	4,016.0	200.0		S2	210			1	
✓66E-04	7,352.0	15,416.0	4,023.0	450.0	132	S2				1	
✓66E-05	7,536.0	15,206.0	4,014.0	346.8	130	S2	210			1	
✓66E-06	7,736.4	15,399.4	4,008.8	500.0	130	S2	210			1	
✓66E-07	7,131.0	15,217.0	4,018.0	504.0	132	S2				1	
✓66E-08	7,141.0	15,619.0	4,012.0	370.5		S2	210			1	
✓66E-09	7,943.0	15,592.0	4,037.0	546.0	130	S2	210			1	
✓67-01	7,745.0	15,805.0	4,013.0	351.5	132	S2				1	
✓67-02	8,171.5	15,753.1	4,123.0	606.0	130	S2	210			1	
✓67-03	8,177.1	14,934.9	4,039.0	999.0	126	S2				1	
✓67-04	8,162.6	15,361.3	4,081.0	742.0	128	S2	210			1	
✓67-05	7,942.0	15,176.7	4,028.0	569.0	128	S2	210			1	
✓67-06	8,566.2	15,016.0	4,135.0	852.5	124	S2				1	
✓67-07	7,743.1	15,007.0	4,005.0	551.0	128	S2				1	
✓67-08	8,342.2	15,602.2	4,164.0	806.0	128	S2				1	
✓67-09	8,740.0	15,199.0	4,186.0	800.0	124	S2	210			1	

05MAR87

!THE IMPERIAL ANVIL!

DRILL HOLE COLLAR DATA (DH021)

PAGE: 2

DDH	UTM-N	UTM-E	UTM-ELEV	TOTAL DEPTH	SECTION	RFE	DIR	PLUNGE	ANGLE	DHD	SSC
✓67-10	8,340.0	15,203.0	4,103.0	741.0	126	S2				1	
✓67-11	8,343.0	14,808.0	4,057.0	723.0	124	S2	210			1	
✓67-12	8,538.0	14,602.0	4,061.0	1,006.0	122+020	S2	235			1	1
✓67-30	8,162.6	14,623.6	4,023.7	661.0	124	S2	210			1	
✓70-12	8,200.3	14,209.7	4,006.7	701.0	122+020	S2	235			1	1
✓70-13	7,561.2	14,814.0	4,011.2	706.0		S2	210			1	
✓70-17	8,596.0	14,209.3	4,019.0	703.0	120+000	S2	235			1	1
✓71-01	8,118.0	13,975.0	3,967.2	695.0	121+000	S2	235			1	1
✓71-02	8,600.0	13,793.0	4,005.0	603.0	118+000	S2	235			1	1
✓71-03	8,397.0	13,997.0	3,992.6	645.0	120+000	S2	235			1	1
✓71-04	7,983.0	14,402.0	3,992.6	570.0	124	S2	210			1	
✓71-05	7,721.0	14,596.0	4,001.5	567.0	126	S2	210			1	
✓71DS-01	6,532.4	13,803.2	3,960.7	999.0	127+200E	S2	210			1	
✓71DS-02	7,336.4	13,800.5	3,960.0	791.0	122+300E	S2	210			1	
✓72-11	8,046.7	16,179.7	4,060.0	287.0		S2	210			1	
✓72-12	7,366.7	15,116.5	4,018.0	393.0	131	S2	210			1	
✓72-13	7,571.6	14,463.6	4,002.0	680.0	126	S2	210			1	
✓72-15	8,569.9	15,442.6	4,188.3	700.0	126	S2	210			1	
✓72-16	8,978.1	15,011.7	4,161.8	810.0	122+020	S2	235			1	1
✓72004	8,801.1	13,597.3	4,036.2	600.0						1	
✓72006	10,029.9	14,241.5	4,129.6	274.0						1	
✓72007	9,804.6	13,996.7	4,040.2	437.0						1	
✓72008	9,524.4	13,743.3	3,995.5	305.0						1	
✓73-01	9,684.3	14,711.2	4,182.6	549.0	117+000	S2	235			1	1
✓73-02	9,254.1	14,275.2	4,060.2	700.0	117+000	S2	235			1	1
✓73003	9,419.6	13,569.6	3,953.0	303.0						1	
✓73027	10,115.0	14,298.6	4,043.0	140.0						1	
✓73028	9,176.4	13,801.5	3,948.2	330.0						1	
✓73029	9,956.6	14,589.8	4,120.0	307.0						1	
✓74-01	9,701.5	14,908.2	4,112.8	523.0	118+000	S2	235			1	1
✓74-02	9,032.6	13,965.5	3,965.5	474.0	117+000	S2	235			1	1
✓74-07	9,398.7	15,001.9	4,138.5	777.0	120+000	S2	235			1	1
✓74-08	8,002.8	14,796.3	4,017.8	576.0	126	S2	210			1	
✓74-10	7,890.6	15,456.5	4,017.3	508.0	130	S2	210			1	
✓74-11	7,682.8	15,538.8	4,017.9	300.0	131	S2	210			1	
✓74-15	9,004.0	14,601.9	4,056.9	754.0	120+000	S2	235			1	1
✓74-16	9,515.6	14,677.1	4,060.7	641.0	118+000	S2	235			1	
✓74-17	8,431.2	14,404.4	4,031.0	585.0	122+020	S2	235			1	1
✓74-18	7,445.1	15,512.9	4,015.5	250.0	132	S2	210			1	
✓74-19	7,431.3	15,336.4	4,016.4	373.0	131	S2	210			1	
✓74-20	7,690.8	15,281.2	4,004.4	427.0	130	S2	210			1	
✓74-21	7,191.9	15,402.4	4,014.0	250.0	133	S2	210			1	
✓74005	9,606.3	14,193.3	3,902.6	325.0						1	
✓74006	9,815.2	14,343.8	3,979.8	407.0						1	
✓74009	9,404.4	13,993.3	3,923.4	311.0						1	
✓74012	9,292.8	13,500.7	3,873.0	167.5						1	
✓74014	9,330.2	13,670.6	3,832.4	176.0						1	
✓75-03	9,214.5	14,972.6	4,139.6	688.0	121+000	S2	235			1	1
✓75-04	7,802.5	15,601.2	4,018.4	482.0	131	S2	210			1	
✓75-05	9,495.1	14,907.1	4,109.7	651.0	119+000	S2	235			1	1
✓75-06	9,285.3	14,516.6	4,042.6	701.0	118+000	S2	235			1	1

DDH	UTM-N	UTM-E	UTM-ELEV	TOTAL DEPTH	SECTION	RFE	DIR	PLUNGE ANGLE	DHD	SSC
✓75-09	9,365.1	14,773.7	4,063.7	723.0	119+000	S2	235		1	1
✓75-10	9,302.4	15,100.8	4,141.0	957.0	121+000	S2	235		1	1
✓75-11	8,878.3	14,097.0	4,000.1	2,120.0	118+000	S2	235		1	1
✓75001	9,431.1	14,149.0	3,832.3	233.0					1	
✓75002	8,997.7	14,399.9	4,025.5	687.0	119+000	S2	235		1	1
✓75007	9,856.4	14,432.6	3,906.0	261.0					1	
✓75008	9,993.7	14,199.6	3,878.7	200.0					1	
✓75456-15	6,791.0	14,397.0	4,018.0	821.0	130	S2	210		1	
✓75456-18	7,603.0	13,966.0	3,981.9	1,410.0	124	S2	210		1	
✓76-01	9,067.7	15,135.1	4,185.6	754.0	122+020	S2	235		1	1
✓76-02	8,892.2	15,099.2	4,181.5	821.0	123+015	S2	235		1	1
✓76-03	8,798.3	15,009.1	4,166.0	866.0	123+015	S2	235		1	1
✓76-04	8,676.0	15,107.6	4,156.9	890.0	124	S2			1	
✓76-05	8,584.0	14,797.0	4,100.2	744.0	123+015	S2	235		1	1
✓76-06	8,805.2	14,600.1	4,058.7	801.0	121+000	S2	235		1	1
✓76-07	8,614.0	14,406.4	4,051.3	787.0	121+000	S2	235		1	1
✓76-08	8,395.3	14,621.1	4,041.9	690.0	123+015	S2	235		1	1
✓76-09	8,199.0	14,420.5	4,012.5	638.0	123+015	S2	235		1	1
✓76-10	8,397.2	14,213.9	4,009.1	626.0	121+000	S2	235		1	1
✓76-11	8,618.1	13,987.0	3,992.0	595.0	119+000	S2	235		1	1
✓76-12	8,993.3	14,806.6	4,069.0	787.0	121+000	S2	235		1	1
✓76-13	9,003.1	14,399.2	4,002.2	714.0	119+000	S2	235		1	1
✓76-14	9,203.0	14,598.0	4,002.6	611.0	119+000	S2	235		1	1
✓76-22	8,799.1	14,227.3	4,012.1	630.0	119+000	S2	235		1	1
✓76916	9,168.9	14,246.5	3,926.1	793.0	117+000	S2	235		1	
✓76X-09	10,152.7	15,300.6	4,173.2	1,237.0	118+000	S2	235		1	1
✓76X-10	9,795.0	14,990.0	4,041.2	637.0	118+000	S2	235		1	1
✓76X-14	9,870.3	15,107.5	4,076.0	829.0	118+000	S2	235		1	1
✓76X-17	9,293.0	15,529.2	4,223.2	464.5	123+015	S2	235		1	1
✓76X-19	8,688.0	16,295.0	4,218.2	881.0	130	S2	210		1	
✓76X-20	9,053.8	15,310.5	4,202.3	847.0	123+015	S2	235		1	1
✓77-01	8,573.3	15,213.8	4,147.4	729.0	125	S2	210		1	
✓77-02	8,468.9	15,315.3	4,140.9	732.0	126	S2			1	
✓77-03	8,380.4	15,406.4	4,118.9	694.0	127	S2			1	
✓77-04	8,168.3	15,578.1	4,117.3	721.0	129	S2	210		1	
✓77-06	8,286.1	15,503.2	4,136.0	700.0	128	S2			1	
✓77-07	8,060.0	15,635.9	4,101.6	604.0	130	S2	210		1	
✓77-09	8,363.5	14,986.3	4,096.7	765.0	125	S2			1	
✓77-10	8,165.0	15,223.0	4,061.6	662.0	127	S2	210		1	
✓77-11	7,876.9	15,729.0	4,021.9	300.0	131	S2			1	
✓77-12	7,802.6	15,208.3	4,014.7	402.0	129	S2	210		1	
✓77-13	7,974.9	14,986.7	4,018.2	543.0	127	S2	210		1	
✓77-14	7,978.7	15,357.8	4,023.4	323.0	129	S2	240		1	
✓77-15	7,794.9	14,799.4	4,016.0	565.0	127	S2			1	
✓77-16	7,986.5	14,589.4	4,007.0	670.0	125	S2	210		1	
✓77-17	8,190.0	14,784.1	4,026.3	650.0	125	S2	210		1	
✓77018	9,790.4	14,417.4	3,831.1	297.0	115				1	
✓77020	9,925.2	14,437.8	3,866.9	95.0	115				1	
✓77021	9,957.9	14,355.8	3,853.0	80.0	114				1	
✓77023	9,877.7	14,682.6	3,839.8	117.0	116				1	
78005	9,282.6	13,918.3	3,748.1	173.0	115				1	

05MAR87

!THE IMPERIAL ANVIL!

DRILL HOLE COLLAR DATA (DH021)

PAGE: 4

DDH	UTM-N	UTM-E	UTM-ELEV	TOTAL DEPTH	SECTION	RFE	DIR	PLUNGE	ANGLE	DHD	SSC
78006 -	9,482.1	13,915.9	3,709.1	4130 59.1	114+000					1	
78022 -	9,698.7	14,293.1	3,712.6	4110 103.0	115					1	
78023 -	9,496.6	14,311.1	3,712.6	4036 123.0	116					1	
78024 -	9,684.9	14,494.2	3,723.1	4111 163.0	116					1	
78025 -	9,508.9	14,078.6	3,696.3	4111 86.0	115					1	
78026 -	9,700.0	14,100.0	3,711.0	4125 121.0	114					1	
78027 -	9,579.2	13,824.2	3,691.3	4152 31.0	113					1	
79-01	9,000.8	14,208.1	3,921.1	576.0	118+000	S2	235			1	1
79-02 -	9,361.1	14,623.7	3,889.5	4152 458.0	118+000	S2	235			1	1
79-03 -	9,491.5	14,715.2	3,879.6	4164 516.0	118+000	S2	235			1	1
80-01	9,136.0	14,402.0	3,905.0	584.0	118+000	S2	235			1	1
80-02	8,305.7	14,914.5	4,061.2	680.0	125	S2	210			1	
80-03	8,299.4	15,116.6	4,086.3	663.0	126	S2				1	
80-04	8,513.9	15,126.1	4,109.2	704.0	125	S2	210			1	
80-05	8,701.0	14,305.3	3,955.0	589.0	120+000	S2	235			1	1
80-06	8,859.7	14,928.0	4,027.5	753.0	122+020	S2	235			1	1
80-07	8,674.8	14,718.2	4,031.2	699.0	122+020	S2	235			1	1
80-08	9,060.8	14,675.2	3,954.5	601.0	120+000	S2	235			1	1
81-01	7,594.5	15,399.6	4,002.9	320.0	131	S2	210			1	
81-02	7,711.3	15,102.5	3,994.5	400.0	129	S2	210			1	
81-03	7,503.2	15,105.3	4,011.6	384.0	130	S2	210			1	
81-04	7,297.5	15,299.4	4,018.7	305.0	132	S2	210			1	
81-05	7,091.8	15,304.1	4,005.8	252.0	133	S2	210			1	
81-06	7,296.6	15,508.9	4,010.5	273.0	133	S2	210			1	
81-07	7,402.5	15,604.1	4,009.8	190.0	133	S2	210			1	
81-08	7,703.7	15,651.8	4,016.4	288.0	132	S2	210			1	
81-09	7,860.4	15,057.8	4,014.9	481.0	128	S2	210			1	
81-10	7,922.9	15,325.7	4,016.1	538.0	129	S2	210			1	
81-11	7,991.9	15,396.3	4,024.9	533.0	129	S2	210			1	
81-12	7,822.6	15,416.8	4,014.7	488.0	130	S2	210			1	
81-13	7,898.9	15,112.8	4,014.1	504.0	128	S2	210			1	
81-14	8,095.1	15,301.6	4,050.0	641.0	128	S2				1	
81-15	8,084.3	15,504.8	4,100.8	685.0	129	S2				1	
81-16	7,843.8	15,662.7	4,013.1	518.0	131	S2				1	
81-18	7,845.7	15,256.9	4,012.4	478.0	129	S2	210			1	
81-19	8,102.2	15,699.7	4,101.3	624.0	130	S2	210			1	
81-20	7,733.0	15,533.0	4,017.9	421.0	131	S2	210			1	
81017 -	7,734.0	15,529.4	4,017.7	4008 248.0	131					1	
82F-01	8,881.5	15,313.2	4,071.3	903.0	124	S2	210			1	
82F-02	8,584.4	15,598.3	4,032.3	755.0	127	S2	210			1	
82F-03	8,218.2	16,073.9	4,036.4	627.0	127+600E	S2	210			1	
82F-04	9,066.5	15,528.7	4,071.2	787.0	124	S2	200			1	
82F-05	7,889.3	14,894.5	3,913.1	407.0	127	S2	210			1	
82F-06	8,467.3	14,924.0	4,069.0	792.0	124	S2	200			1	
82F-07	7,890.6	14,693.4	3,912.8	422.0	126	S2				1	
82F-08	8,091.1	14,697.7	3,908.9	541.0	125	S2	200			1	
82F-09	8,296.2	14,692.8	4,040.1	667.0	124	S2	210			1	
82F-10	7,792.2	14,389.4	3,940.6	627.0	125	S2	210			1	
82F-11	8,094.9	14,491.6	4,009.4	603.6	124	S2	210			1	
82F-12	7,283.0	14,897.5	3,875.4	451.0	130	S2	210			1	
82F-13	7,870.9	14,270.2	3,946.6	641.0	124	S2	210			1	

DDH	UTM-N	UTM-E	UTM-ELEV	TOTAL DEPTH	SECTION	RFE	DIR	PLUNGE ANGLE	DHD	SSC
82F-14	7,517.5	14,524.1	3,992.1	700.0	127	S2	210		1	
82F-15	7,087.1	14,693.1	4,025.6	740.0	130	S2	210		1	
82F-16	7,390.8	14,399.0	4,004.4	707.0	127	S2	210		1	
82F-17	7,695.4	14,898.2	3,912.9	400.0	128	S2	210		1	
82F-22-	5,158.4	14,959.7	4,022.5	3880 377.0	140				1	
82F-24-	6,646.4	15,322.0	4,007.4	3998 127.0	135	S2			1	
83F-01	6,783.0	14,782.1	4,035.5	656.5	132+00E	S2	210		1	
83F-02	6,577.2	14,564.5	4,023.0	893.0	132+00E	S2	210		1	
83F-03	8,218.2	16,073.8	4,036.3	213.0	131 127+600E	S2	210		1	
83F-04-	6,357.4	14,356.4	4,016.9	4000 800.7	132+00E	S2	210		1	
83F-05-	8,136.1	16,131.8	4,039.7	4071 200.0	132+00E	S2	210		1	
83F-06-	8,068.7	16,204.2	4,039.3	4058 196.0	132+100E	S2	210		1	
83F-07-	6,641.7	15,201.5	4,013.7	4005 202.0	134 132+100E	S2	210		1	
83F-08-	6,125.0	14,587.4	4,021.7	3998 690.0	134 132+300E	S2	210		1	
83F-09-	6,645.6	15,039.6	4,018.1	4013 493.0	134 132+300E	S2	210		1	
83F-10-	5,689.5	14,541.0	3,981.1	3973 727.0	136 132+600E	S2	210		1	
83F-11-	6,517.8	15,193.3	4,005.0	4002 212.0	135 132+500E	S2	210		1	
83F-12-	6,860.6	14,280.4	4,004.7	4005 832.0	129 127+300E	S2	210		1	
83F-13-	6,789.0	15,213.7	3,985.4	4006 200.0	134 132+300E	S2	210		1	
83F-14-	6,750.3	15,309.6	3,985.5	3985 198.5	135 132+400E	S2	210		1	
83F-15-	7,078.3	14,504.0	4,013.0	4012 759.0	129 127+300E	S2	210		1	
83F-16-	6,713.9	15,410.5	3,984.9	3997 196.0	135 132+500E	S2	210		1	
83F-17-	6,650.4	15,501.8	3,986.9	3993 200.0	136 132+600E	S2	210		1	
83F-18-	6,573.2	15,274.2	4,006.5	3992 171.0	135 132+500E	S2	210		1	
83F-19-	7,346.4	14,193.2	3,988.6	3989 787.0	126 122+600E	S2	210		1	
83F-20-	6,482.3	15,145.2	4,005.4	4001 197.0	135 132+500E	S2	210		1	
83F-21-	6,571.3	15,137.8	4,017.4	4005 136.5	135 132+400E	S2	210		1	
83F-22-	7,143.7	13,992.6	3,989.6	3975 917.0	126 122+600	S2	210		1	
84F-01	9,090.3	14,515.3	3,810.0	516.0	119+000	S2	235		1	1
84F-02	7,557.8	13,989.6	3,985.5	855.0	122+300E	S2	210		1	
84F-03	9,277.7	14,732.1	3,791.7	381.0	119+000	S2	235		1	1
84F-04	7,355.1	13,783.6	3,960.3	923.0	122+300E	S2	210		1	
84F-05	9,442.8	14,851.5	3,776.6	460.0	119+000	S2	235		1	1
84F-06	9,295.8	14,499.3	3,690.4	301.0	118+000	S2	235		1	1
84F-07	6,374.3	14,799.6	4,009.2	626.0	132+300E	S2	210		1	
84F-08	9,597.3	14,999.4	3,758.7	280.0	119+000	S2	235		1	1
84F-09	6,504.6	14,501.2	4,020.6	814.0	132+000E	S2	210		1	
84F-10	7,362.1	14,790.8	3,886.3	525.0	127+300E	S2	210		1	
84F-11	10,358.3	12,067.2	4,320.2	550.0	97+500E	S2	210		1	
84F-12	10,211.4	12,208.3	4,306.7	550.0	102+000E	S2	210		1	
84F-13	7,054.9	15,127.6	3,872.5	210.0	132+052E	S2	210		1	
84F-14	7,186.1	15,019.7	3,870.6	335.0	131+022E	S2	210		1	
84F-15	6,552.2	16,103.7	3,987.8	141.0	139+000E	S2	210		1	
84F-16	6,753.3	16,210.3	4,001.9	150.0	139+000E	S2	210		1	
84F-17	7,287.9	15,117.1	3,871.1	227.0	131+022E	S2	210		1	
84F-18	8,715.3	14,518.6	3,915.6	585.0	121+000	S2	235		1	1
84F-19	8,896.6	14,700.0	3,913.8	597.0	121+000	S2	235		1	1
84F-20	9,099.0	14,901.6	3,912.5	556.0	121+000	S2	235		1	1
84F-21	9,503.5	15,296.3	3,908.4	397.0	121+000	S2	235		1	1
84F-22	9,701.1	15,096.5	3,752.0	185.0	119+000	S2	235		1	1
84F-23	8,513.0	14,728.7	3,909.7	572.0	123+000	S2	235	210	1	1

DDH	UTM-N	UTM-E	UTM-ELEV	TOTAL DEPTH	SECTION	RFE	DIR	PLUNGE	ANGLE	DHD	SSC
84F-24	8,082.8	14,307.2	3,910.1	545.0	123+000	S2	235			1	1
84F-25	8,690.0	14,912.0	3,911.0	591.0	123+015	S2	235			1	1
84F-26	8,986.0	15,204.3	3,912.2	504.0	123+015	S2	235			1	1
84F-27	9,188.5	15,400.9	3,914.4	355.0	123+015	S2	235			1	1
84F-28	8,969.9	16,296.9	4,254.0	350.0	129+000	S2	210			1	
86F-01	9,500.0	14,750.0	3,726.0	209.0	118+070	S2	235		315	1	1
86F-02	7,652.0	15,482.0	3,876.0	160.0	131+022	S2	235		315	1	1
86F-03	7,650.0	15,350.0	3,874.5	161.0	130+000	S2	235		315	1	1
86F-04	6,610.0	15,225.0	4,014.0	135.0		S2	235		315	1	1
86F-05	9,616.3	14,880.0	3,737.9	272.0	118+070	S2	235		315	1	1
86F-06	9,407.0	14,667.5	3,713.7	364.0	118+070	S2	235		315	1	1
86F-07	8,901.6	14,321.1	3,838.6	547.0	119+000	S2	235		315	1	1
86F-08	8,293.4	14,511.6	3,870.1	492.0	123+000	S2	235		315	1	1
86F-09	8,438.0	14,223.2	3,869.5	476.0	121+000	S2	235		315	1	1
86F-10	8,546.0	13,949.8	3,873.9	522.0	119+000	S2	235		315	1	1
86F-11	9,114.9	14,711.4	3,739.5	337.0	120+000	S2	235		315	1	1
86F-12	8,993.8	14,596.9	3,740.5	463.0	120+000	S2	235		315	1	1
86F-13	8,993.8	14,596.9	3,740.5	412.0	120+000	S2	235		315	1	1
86F-14	9,361.6	14,564.2	3,706.9	270.0	118+000	S2	235		315	1	1
86F-15	8,757.8	14,787.0	3,737.5	416.5	121+000	S2	235		315	1	1
86F-16	9,426.4	14,738.8	3,706.7	297.0	118+00	S2	235		315	1	1
86F-17	9,534.4	14,831.4	3,708.7	325.0	118+070	S2	235		315	1	1
86F-18	9,363.8	14,961.4	3,704.5	277.0	120+000	S2	235		315	1	1
86F-19	9,300.0	14,898.0	3,702.6	313.0	120+000	S2	235		315	1	1
86F-20	9,350.7	14,843.4	3,705.4	257.0	119+070	S2	235		315	1	1
86F-21	9,420.2	14,923.7	3,708.4	299.0	119+070	S2	235		315	1	1
86F-22	9,260.3	14,657.5	3,708.4	327.0	119+000	S2	235		315	1	1
86F-23	9,181.7	14,980.9	3,705.1	387.0	121+000	S2	235		315	1	1
86F-24	9,051.2	14,853.9	3,710.2	391.0	121+000	S2	235		315	1	1
86F-25	8,979.0	14,772.6	3,713.0	411.0	121+000	S2	235		315	1	1

**THIS REPORT WAS REQUESTED BY: LEEP .GEOLOGY AT: 23:26:41

PAGE: 1

DDH: 65006 UTM-N: 9599.6 UTM-E: 14399.9 UTM-ELEV: 4099.8 TOTAL DEPTH: 500.0 SECTION:
RFE: RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	---ASSAYS---													
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %
284.0	290.0	70004	6.0	.0	****	.50	.07	2.30	4.30	19.20										
290.0	295.0	70005	5.0	.0	****	.50		.40	5.40	30.20										
295.0	300.0	70006	5.0	.0	****	.50	.07	1.10	4.00	30.90										
300.0	305.0	70007	5.0	.0	****	.50	.15	1.50	4.20	30.20										
305.0	310.0	70008	5.0	.0	****	.50	.01	2.50	7.60	80.90										
310.0	315.0	70009	5.0	.0	****	.50		3.90	9.20	78.20										
315.0	320.0	70010	5.0	.0	****	.50	.07	2.10	4.10	12.30										
320.0	325.0	70011	5.0	.0	****	.50	.07	3.40	3.10	8.20										
325.0	330.0	70012	5.0	.0	****	.50	.16	1.70	1.60	8.20										
330.0	335.0	70013	5.0	.0	****	.50	.07	1.70	1.60	3.40										
335.0	340.0	70014	5.0	.0	****	.50			.70											
340.0	345.0	70015	5.0	.0	****	.50		.20	.20											
345.0	350.0	70016	5.0	.0	****	.50		3.90	3.20											
350.0	355.0	70017	5.0	.0	****	.50	.18	5.50	6.80	5.50										
355.0	360.0	70018	5.0	.0	****	.50	2.60	2.30	2.70	6.80										
360.0	365.0	70019	5.0	.0	****	.50		.70	2.50											
365.0	370.0	70020	5.0	.0	****	.50	.22	4.40	2.60	13.70										
370.0	375.0	70021	5.0	.0	****	.50		1.00	8.60	6.80										
375.0	380.0	70022	5.0	.0	****	.50	.27	1.60	4.40	12.30										
380.0	385.0	70023	5.0	.0	****	.50		.50	.70											
385.0	390.0	70024	5.0	.0	****	.50	.18	6.40	11.80	6.80										
390.0	395.0	70025	5.0	.0	****	.50	.37	1.60	3.60											
395.0	400.0	70026	5.0	.0	****	.50	.30	3.60	7.50											
400.0	405.0	70027	5.0	.0	****	.50		3.10	6.80											
405.0	410.0	70028	5.0	.0	****	.50	.07	4.70	9.60	8.20										
410.0	415.0	70029	5.0	.0	****	.50	.15	5.20	11.50	8.20										
415.0	420.0	70030	5.0	.0	****	.50		4.60	9.80	6.80										
420.0	425.0	70031	5.0	.0	****	.50		2.40	5.10	4.10										
425.0	430.0	70032	5.0	.0	****	.50		3.70	8.20	6.80										
430.0	435.0	70033	5.0	.0	****	.50		4.00	7.70	12.30										
435.0	440.0	70034	5.0	.0	****	.50		4.30	9.60	2.70										
440.0	445.0	70035	5.0	.0	****	.50		4.40	9.20	5.50										
445.0	450.0	70036	5.0	.0	****	.50		3.60	7.10	17.80										
450.0	455.0	70037	5.0	.0	****	.50		3.30	7.10	6.80										
455.0	460.0	70038	5.0	.0	****	.50		2.10	3.80											
460.0	465.0	70039	5.0	.0	****	.50		.40	1.10											
465.0	470.0	70040	5.0	.0	****	.50		2.80	6.20	5.50										
470.0	475.0	70041	5.0	.0	****	.50		3.00	7.50	13.70										
475.0	480.0	70042	5.0	.0	****	.50		2.90	5.20	30.20										
480.0	485.0	70043	5.0	.0	****	.50	.22	.70	1.70	12.30										

-----DEPTHS----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
146.0	150.0	70048	4.0	.0	****	.50	.52	2.30	6.30	22.00											
150.0	155.0	70049	5.0	.0	****	.50	.01	.30	1.00	20.60											
155.0	160.0	70050	5.0	.0	****	.50	.01	1.40	4.20	6.90											
160.0	165.0	70051	5.0	.0	****	.50	.01	2.70	4.40	11.00											
165.0	170.0	70052	5.0	.0	****	.50	.37	2.10	5.70	18.50											
185.0	190.0	70054	5.0	.0	****	.50	.07	2.00	4.40	15.80											
190.0	195.0	70055	5.0	.0	****	.50	.01	2.30	8.50	15.10											
195.0	200.0	70056	5.0	.0	****	.50	.01	4.10	9.50	22.00											
200.0	205.0	70057	5.0	.0	****	.50		2.40	5.30	22.00											
205.0	210.0	70058	5.0	.0	****	.50		3.70	12.20	36.40											
210.0	215.0	70059	5.0	.0	****	.50		2.80	7.60	26.10											
215.0	220.0	70060	5.0	.0	****	.50		2.60	5.50	18.50											
220.0	225.0	70061	5.0	.0	****	.50	.01	1.80	11.10	27.40											
225.0	235.0	70062	10.0	.0	****	.50	.01	1.50	2.80	53.50											
235.0	240.0	70063	5.0	.0	****	.50	.01	3.90	5.00	11.00											
240.0	245.0	70064	5.0	.0	****	.50	.01	1.80	5.80	11.00											
245.0	250.0	70065	5.0	.0	****	.50	.01	2.30	7.80	19.20											
250.0	255.0	70066	5.0	.0	****	.50		4.80	9.40	37.70											
255.0	260.0	70067	5.0	.0	****	.50	.01	1.60	5.50	13.00											
260.0	265.0	70068	5.0	.0	****	.50		3.00	8.70	19.20											
265.0	270.0	70069	5.0	.0	****	.50		1.80	5.90	19.90											
270.0	275.0	70070	5.0	.0	****	.50		3.60	9.70	34.30											
275.0	280.0	70071	5.0	.0	****	.50		2.70	7.50	57.60											
280.0	285.0	70072	5.0	.0	****	.50	.01	2.10	6.00	19.20											
285.0	290.0	70073	5.0	.0	****	.50	.01	2.30	6.80	16.50											
290.0	295.0	70074	5.0	.0	****	.50	.15	.01	2.20	.10											
295.0	300.0	70075	5.0	.0	****	.50	.01	.60	2.50	8.20											
330.0	335.0	70077	5.0	.0	****	.50	.07	1.60</													

DDH: 65009 UTM-N: 9199.8 UTM-E: 13998.3 UTM-ELEV: 4060.5 TOTAL DEPTH: 472.0 SECTION:
 RFE: RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
345.0	350.0	70114	5.0	.0	****	2.86	.24	.26	.57	6.00			5	5	11	.21		.12			
350.0	355.0	70115	5.0	.0	****	3.02	.24	.86	3.01	9.00			6	17	24	.13		.14			
355.0	360.0	70116	5.0	.0	****	3.25	.07	3.13	3.87	35.00			6	17	24	4.39		.14			
360.0	365.0	70117	5.0	.0	****	4.71	.19	5.00	6.52	70.00			6	17	24	16.14		.14			
365.0	370.0	70118	5.0	.0	****	4.44	.21	5.03	7.28	62.00			6	17	24	.17		.14			
370.0	375.0	70119	5.0	.0	****	4.15	.42	4.87	6.89	57.00			11	21	33	1.83		.16			
375.0	380.0	70120	5.0	.0	****	4.29	.45	3.04	5.44	46.00			11	21	33	8.32		.16			
380.0	385.0	70121	5.0	.0	****	4.54	.13	4.72	7.45	57.00			11	21	33	3.98		.16			
385.0	390.0	70122	5.0	.0	****	4.46	.09	5.18	6.82	49.00			11	21	33	.05		.16			
390.0	395.0	70123	5.0	.0	****	4.16	.12	3.72	5.92	30.00			11	25	37	.07		.12			
395.0	400.0	70124	5.0	.0	****	4.26	.13	5.63	5.02	58.00			11	25	37	.07		.12			
400.0	405.0	70125	5.0	.0	****	4.46	.57	5.50	7.81	54.00			11	25	37	.09		.12			
405.0	410.0	70126	5.0	.0	****	4.63	.25	5.30	7.21	44.00			11	25	37	.14		.12			
410.0	415.0	70127	5.0	.0	****	4.58	.21	6.01	7.28	47.00			7	25	32	.07		.14			
415.0	420.0	70128	5.0	.0	****	4.76	.23	4.71	5.21	47.00			7	25	32	9.08		.14			
420.0	425.0	70129	5.0	.0	****	4.53	.22	2.28	1.92	24.00			7	25	32	.07		.14			
425.0	430.0	70130	5.0	.0	****	3.67	.28	5.62	13.10	54.00			7	25	32	1.19		.14			
430.0	435.0	70131	5.0	.0	****	2.91	.09	1.46	4.13	26.00			3	2	6	.22		.05			
435.0	440.0	70132	5.0	.0	****	3.30	.06	17.60	2.51	82.00			3	2	6	.15		.05			
440.0	445.0	70133	5.0	.0	****	2.75	.06	1.33	2.68	23.00			3	2	6	.17		.05			
445.0	450.0	70134	5.0	.0	****	2.64	.05	1.38	2.76	24.00			3	2	6	.16		.05			
450.0	455.0	70135	5.0	.0	****	3.04	.09	3.92	3.67	67.00			6	6	12	.25		.06			
455.0	460.0	70136	5.0	.0	****	3.08	.09	9.11	5.68	139.00			6	6	12	.18		.06			
460.0	465.0	70137	5.0	.0	****	3.26	.36	1.53	4.51	36.00			6	6	12	.21		.06			
465.0	472.0	70138	7.0	.0	****	2.85	.13	1.37	3.33	29.00			6	6	12	.18		.06			

PAGE: 5

[illegible]

DDH: 66-03 UTM-N: 9200.0 UTM-E: 14398.0 UTM-ELEV: 4100.4 TOTAL DEPTH: 744.0 SECTION: 118+000
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

-----DEPTHS-----						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
548.8	553.0	70219	4.2	.0	2C0(	2.82	.10	.56	1.46	7.10			5	8	14	.31		.10			
553.0	558.0	70220	5.0	.0	2D4	3.30	.14	2.49	8.93	31.50			5	8	14	.09		.10			
558.0	563.0	70221	5.0	.0	2D4	3.33	.18	3.56	11.43	47.20			5	8	14	.10		.10			
563.0	568.0	70222	5.0	.0	2F49	3.87	.32	4.38	8.13	71.60			5	8	14	.13		.10			
568.0	573.0	70223	5.0	.0	2F49	4.88	.31	6.29	6.43	86.80			8	23	31	.08		.40			
573.0	578.0	70224	5.0	.0	2F49	4.95	.27	7.30	7.46	98.90			8	23	31	.06		.40			
578.0	583.0	70225	5.0	.0	2F46	4.95	.20	5.69	6.36	99.70			8	23	31	.29		.40			
583.0	586.0	70226	3.0	.0	2F49	4.46	.34	7.17	7.14	89.70			8	23	31	.08		.40			
586.0	590.6	70227	4.6	.0	2A0(	2.95	.11	1.20	.92	32.80			8	23	31	2.44		.40			
590.6	595.0	70228	4.4	.0	2A0(	2.97	.12	1.90	1.80	30.80			4	4	8	3.02		.16			
595.0	600.0	70229	5.0	.0	2B0(	3.13	.07	1.72	1.68	30.90			4	4	8	4.83		.16			
600.0	605.0	70230	5.0	.0	2D0(	3.07	.07	1.24	1.96	13.20			4	4	8	3.29		.16			
605.0	610.0	70231	5.0	.0	2B6	2.94	.02	.44	.86	7.00			4	4	8	4.32		.16			
610.0	615.0	70232	5.0	.0	2D6(	3.01	.05	.98	1.40	18.80			4	7	12	3.77		.10			
615.0	620.0	70233	5.0	.0	2D6(	2.90	.09	1.20	3.01	26.90			4	7	12	2.69		.10			
620.0	624.0	70234	4.0	.0	2D0	3.05	.11	1.48	4.57	35.30			4	7	12	.33		.10			
624.0	629.0	70235	5.0	.0	2D4(	3.93	.22	9.45	9.51	152.00			4	7	12	.15		.10			
629.0	634.0	70236	5.0	.0	2D4(	4.15	.15	5.50	7.80	72.70						.12					
634.0	639.0	70237	5.0	.0	2C0(	4.15	.07	.50	.70	4.10						.12					
639.0	644.0	70238	5.0	.0	2D9(	4.15	.24	2.60	2.70	20.60						.12					
644.0	649.0	70239	5.0	.0	2D9(	4.15	.19	3.60	4.80	20.60						.12					
649.0	654.0	70240	5.0	.0	2D9(	4.80	.21	2.86	3.56	29.70			15	27	42	.09		.19			
654.0	659.0	70241	5.0	.0	2E9(	4.56	.29	2.30	.94	23.90			15	27	42	.04		.19			
659.0	664.0	70242	5.0	.0	2A4&	4.29	.33	1.06	2.29	15.80			15	27	42	.03		.19			
664.0	669.0	70243	5.0	.0	2A4&	3.23	.23	2.41	1.65	13.10			15	27	42	.05		.19			
669.0	674.0	70244	5.0	.0	2E19	4.26	.32	1.68	1.42	23.80			10	31	41	.04		.12			
674.0	679.0	70245	5.0	.0	2E19	4.57	.32	2.00	3.90	17.10			10	31	41	.02		.12			
679.0	684.0	70246	5.0	.0	2A4(	4.58	.16	3.42	4.18	67.30			10	31	41	.04		.12			
684.0	689.0	70247	5.0	.0	2A4(	4.26	.22	2.43	2.37	14.20			10	31	41	.06		.12			
689.0	694.0	70248	5.0	.0	2A4(	4.80	.11	3.30	4.81	17.40			3	16	19	.02		.06			
694.0	699.0	70249	5.0	.0	2A4(	3.32	.23	1.88	5.79	29.90			3	16	19	.09		.06			
699.0	704.0	70250	5.0	.0	2A0(	2.81	.07	1.36	2.54	30.40			3	16	19	.21		.06			
704.0	709.0	70251	5.0	.0	2A4(	2.93	.05	.90	3.51	30.20			3	16	19	.23		.06			
709.0	714.0	70252	5.0	.0	2A4(	2.78	.06	1.12	3.09	17.20			2	15	18	.22		.04			
714.0	719.0	70253	5.0	.0	2A4(	2.68	.09	1.14	4.63	54.80			2	15	18	.34		.04			
719.0	724.0	70254	5.0	.0	2A4(	4.25	.34	5.05	9.02	86.20			2	15	18	.06		.04			
724.0	729.0	70255	5.0	.0	2A4(	4.13	.13	2.56	5.79	29.60			2	15	18	.10		.04			
729.0	734.0	70256	5.0	.0	2A4(	3.01	.17	1.80	3.93	24.60			2	15	18	.21		.04			
734.0	739.0	70257	5.0	.0	2A0(	2.90		.20	1.30	6.20			2	15	18	.20		.04			

DDH: 66-05 UTM-N: 8800.1 UTM-E: 13999.5 UTM-ELEV: 4018.1 TOTAL DEPTH: 673.2 SECTION: 118+000
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

-----DEPTHS-----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
489.0	494.0	70320	5.0	.0	2A0	3.04	.06	.34	.96	9.20			3	7	10	.11		.07			
494.0	499.0	70321	5.0	.0	2A0	3.20	.10	.40	.92	10.80			3	7	10	.13		.07			
499.0	504.0	70322	5.0	.0	2A0	3.04	.08	1.36	1.77	18.20			3	7	10	.07		.07			
504.0	509.0	70323	5.0	.0	2A0	2.52	.03	.88	2.86	13.20			3	7	10	.32		.07			
509.0	514.0	70324	5.0	.0	2A4	3.09	.05	1.28	4.00	22.10			4	11	16	.19		.06			
514.0	519.0	70325	5.0	.0	2F40	4.07	.09	5.21	9.11	65.20			4	11	16	.09		.06			
519.0	524.0	70326	5.0	.0	2C00	2.86	.16	1.68	2.20	33.40			4	11	16	.34		.06			
524.0	529.0	70327	5.0	.0	2C00	3.17	.18	.96	1.98	31.10			4	11	16	.38		.06			
529.0	534.0	70328	5.0	.0	2D0	3.43	.14	2.79	7.00	50.20			4	8	13	.16		.04			
534.0	539.0	70329	5.0	.0	2E40	3.21	.21	1.94	3.93	35.30			4	8	13	.16		.04			
539.0	544.0	70330	5.0	.0	2A0	2.82	.10	.74	2.03	14.20			4	8	13	.19		.04			
544.0	549.0	70331	5.0	.0	2A0	2.88	.04	1.10	1.82	29.30			4	8	13	.20		.04			
549.0	554.0	70332	5.0	.0	2A0	2.60	.14	2.08	1.36	29.30			4	8	13	.20		.04			

DDH: 66-06 UTM-N: 9599.5 UTM-E: 14800.0 UTM-ELEV: 4188.3 TOTAL DEPTH: 766.0 SECTION: 118+000
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

-----DEPTHS-----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
423.5	428.3	70337	4.8	.0	2D34	3.96	.16	2.80	7.90	109.70			3	17	20	.20		.06			
437.0	441.0	70339	4.0	.0	2H10	3.14	.01	2.50	2.60	69.90			12	18	30	.20		.09			
456.0	460.0	70341	4.0	.0	2E00	3.10	.16	.93	3.15	20.40			4	22	26	.18		.07			
460.0	465.0	70342	5.0	.0	2D48	3.28	.19	2.89	9.07	40.10			4	22	26	.20		.07			
465.0	470.0	70343	5.0	.0	2E40	4.60	.28	2.84	4.91	52.60			4	22	26	.06		.07			
470.0	475.0	70344	5.0	.0	2E00	4.56	.19	.35	1.36	8.70			4	22	26	.07		.07			
475.0	480.0	70345	5.0	.0	2D40	4.00	.27	3.29	6.91	29.80			4	22	26	.10		.07			
480.0	485.0	70346	5.0	.0	2D00	3.71	.06	1.35	3.38	15.60			3	26	30	.12		.09			
485.0	490.0	70347	5.0	.0	2E10	3.59	.04	1.00	2.80	14.60			3	26	30	.09		.09			
490.0	495.0	70348	5.0	.0	2E81	4.04	.29	.30	.84	19.10			3	26	30	.04		.09			
495.0	500.0	70349	5.0	.0	2E81	3.89	.29		.86	7.10			3	26	30	.03		.09			
500.0	505.0	70350	5.0	.0	2E81	4.06	.31	.69	1.66	9.30			3	26	30	.03		.15			
505.0	510.0	70351	5.0	.0	2E81	4.10	.22	.51	1.04	6.60			3	26	30	.02		.15			
510.0	515.0	70352	5.0	.0	2E81	3.93	.23	.93	1.92	13.70			3	26	30	.05		.15			
515.0	520.0	70353	5.0	.0	2A40	3.81	.09	3.53	7.29	146.00			3	26	30	.10		.15			
520.0	524.0	70354	4.0	.0	2A40	3.22	.14	3.26	4.60	55.20			4	17	21	.17		.11			
524.0	529.0	70355	5.0	.0	2C3	3.32	.23	1.89	1.64	40.50			4	17	21	.11		.11			
529.0	534.0	70356	5.0	.0	2D00	3.69	.16	2.90	2.35	46.70			4	17	21	.10		.11			
534.0	539.0	70357	5.0	.0	2C30	3.74	.14	.56	1.56	14.00			4	17	21	.08		.11			
539.0	544.0	70358	5.0	.0	2C3	3.88	.12	.55	1.80	11.50			2	27	29	.05		.06			
544.0	549.0	70359	5.0	.0	2C30	4.57	.07	.10	1.74	3.90			2	27	29	.04		.06			
549.0	554.0	70360	5.0	.0	2D3	4.17	.10	1.63	4.58	11.30			2	27	29	.05		.06			
554.0	559.0	70361	5.0	.0	2D3	4.29	.25	2.22	2.84	22.00			2	27	29	.03		.06			
559.0	564.0	70362	5.0	.0	2D48	3.71	.07	4.43	7.87	16.00			2	21	24	.06		.03			
564.0	569.0	70363	5.0	.0	2D3	3.94	.08	1.82	5.80	12.10			2	21	24	.06		.03			
569.0	574.0	70364	5.0	.0	2D45	3.55	.10	3.10	11.22	12.50			2	21	24	.14		.03			
574.0	579.0	70365	5.0	.0	2D43	4.07	.05	4.82	9.17	16.10			2	21	24	.05		.03			
579.0	584.0	70366	5.0	.0	2D48	3.75	.07	4.65	10.19	16.50			3	23	26	.06		.05			
584.0	589.0	70367	5.0	.0	2D48	3.62	.04	5.66	11.10	12.70			3	23	26	.09		.05			
589.0	594.0	70368	5.0	.0	2E41	4.00	.04	2.06	6.18	7.60			3	23	26	.06		.05			
594.0	599.0	70369	5.0	.0	2E41	4.25	.06	2.14	4.90	8.20			3	23	26	.03		.05			
599.0	604.0	70370	5.0	.0	2D43	3.70	.05	3.74	9.66	21.70			3	17	21	.10		.04			
604.0	609.0	70371	5.0	.0	2D43	3.44	.06	2.00	7.14	16.00			3	17	21	.17		.04			
609.0	614.0	70372	5.0	.0	2E48	4.22	.04	1.76	5.56	20.30			3	17	21	.08		.04			
614.0	619.0	70373	5.0	.0	2D00	3.13	.18	2.69	5.95	73.70			3	17	21	.27		.04			
619.0	622.8	70374	3.8	.0	2D00	3.07	.07	1.33	4.01	22.60			3	17	21	.32		.04			

DDH: 66-07 UTM-N: 9200.6 UTM-E: 14798.3 UTM-ELEV: 4156.7 TOTAL DEPTH: 810.0 SECTION: 120+000
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

-----DEPTHS-----						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
588.0	593.0	70382	5.0	.0	2E48	4.18	.07	5.35	6.20	54.30			7	22	30	.16		.13			
593.0	598.0	70383	5.0	.0	2E48	4.16	.09	2.88	3.87	26.00			7	22	30	.10		.13			
598.0	603.0	70384	5.0	.0	2E30	3.93	.07	1.78	2.30	19.50			7	22	30	.08		.13			
603.0	608.0	70385	5.0	.0	2D40	3.60	.17	3.26	5.90	15.10			7	22	30	.07		.13			
608.0	613.0	70386	5.0	.0	2D49	3.97	.21	3.84	9.76	13.80			4	25	30	.05		.16			
613.0	618.0	70387	5.0	.0	2E89	4.32	.25	1.18	2.84	7.80			4	25	30	.02		.16			
618.0	623.0	70388	5.0	.0	2D4	4.84	.13	4.13	8.36	10.00			4	25	30	.02		.16			
623.0	628.0	70389	5.0	.0	2F41	4.39	.06	4.51	12.51	13.60			4	25	30	.05		.16			
628.0	633.0	70390	5.0	.0	2D40	3.39	.02	3.97	8.36	20.00			4	20	24	.06		.04			
633.0	638.0	70391	5.0	.0	2D40	4.01	.02	2.78	6.58	14.00			4	20	24	.09		.04			
638.0	643.0	70392	5.0	.0	2E40	4.55	.16	8.34	19.56	47.00			4	20	24	.06		.04			
643.0	648.0	70393	5.0	.0	2F40	3.67	.06	3.78	10.87	27.40			4	20	24	.17		.04			
648.0	658.0	70394	10.0	.0	2C0	3.03	.06	.96	2.24	19.20			3	13	17	.27		.03			
658.0	663.0	70395	5.0	.0	2C0	3.20	.16	.35	2.36	9.50			3	13	17	.20		.03			
663.0	668.0	70396	5.0	.0	2A30	3.24	.04	.25	1.66	18.50			3	13	17	.17		.03			
668.0	673.0	70397	5.0	.0	2A30	3.40	.04	1.06	1.46	29.00			3	13	17	.23		.04			
673.0	678.0	70398	5.0	.0	2D00	2.95	.12	1.76	4.33	22.70			3	13	17	.22		.04			

DDH: 66-10 UTM-N: 8790.5 UTM-E: 14795.4 UTM-ELEV: 4121.4 TOTAL DEPTH: 849.0 SECTION: 122+020
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

-----DEPTHS-----		-----ASSAYS-----																			
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
570.0	575.0	70470	5.0	.0	2D49	4.03	.26	4.56	6.10	79.20			10	8	19	1.77		.18			
575.0	580.0	70471	5.0	.0	2E43	3.33	.17	4.25	4.65	94.00			10	8	19	4.47		.18			
580.0	585.0	70472	5.0	.0	2C30	2.82	.05	.50	.48	15.70			10	8	19	1.21		.18			
585.0	590.0	70473	5.0	.0	2K0*	2.76	.10	.40	.24	10.80			10	8	19	2.42		.18			
590.0	595.0	70474	5.0	.0	2E13	3.91	.46	2.00	1.24	41.50			5	32	37	.20		.12			
595.0	600.0	70475	5.0	.0	2E40	4.66	.10	4.56	4.08	53.30			5	32	37	.05		.12			
600.0	605.0	70476	5.0	.0	2E08	3.95	.07	1.64	1.10	22.10			5	32	37	.06		.12			
605.0	610.0	70477	5.0	.0	2E98	4.57	.20	1.60	.78	22.90			5	32	37	.05		.12			
610.0	615.0	70478	5.0	.0	2E98	4.94	.21	1.20	.46	26.40			2	36	39	.09		.05			
615.0	620.0	70479	5.0	.0	2E08	4.60	.11	1.30	.46	18.40			2	36	39	.04		.05			
620.0	625.0	70480	5.0	.0	2E08	3.80	.18	1.22	.82	63.80			2	36	39	.89		.05			
625.0	630.0	70481	5.0	.0	2E08	4.34	.19	1.14	.64	21.80			2	36	39	.05		.05			
630.0	634.0	70482	4.0	.0	2E08	4.73	.15	.94	1.16	17.10			3	35	39	.88		.08			
634.0	638.0	70483	4.0	.0	2E08	4.17	.15	1.52	1.83	21.70			3	35	39	1.23		.08			
638.0	639.0	70484	1.0	.0	2E08	.50	.15	1.52	1.83	21.70			3	35	39	1.23		.08			
639.0	644.0	70485	5.0	.0	2E19	5.05	.23	2.91	4.57	29.40			2	31	33	2.48		.10			
644.0	649.0	70486	5.0	.0	2G4	4.64		2.75	5.98	27.60			2	31	33	24.07		.10			
649.0	654.0	70487	5.0	.0	2G40	4.69	.14	2.67	4.01	30.00			2	31	33	5.95		.10			
654.0	659.0	70488	5.0	.0	2E08	4.60	.12	2.03	2.23	21.70			2	33	36	2.29		.10			
659.0	664.0	70489	5.0	.0	2E00	3.90	.06	.40	.22	5.30			2	33	36	.13		.10			
664.0	669.0	70490	5.0	.0	2E00	4.21	.12	.94	.67	15.80			2	33	36	.06		.10			
669.0	674.0	70491	5.0	.0	2E49	4.52	.26	3.44	3.55	50.00			2	33	36	.07		.10			
674.0	679.0	70492	5.0	.0	2E41	4.64	.30	3.58	3.16	41.10			3	34	37	.12		.10			
679.0	684.0	70493	5.0	.0	2E49	4.88	.29	3.61	2.92	45.00			3	34	37	.09		.10			
684.0	689.0	70494	5.0	.0	2E08	4.93	.17	2.11	1.29	26.30			3	34	37	.63		.10			
689.0	694.0	70495	5.0	.0	2G0	4.41	.16	3.06	4.61	83.30			3	34	37	15.63		.10			
694.0	699.0	70496	5.0	.0	2E49	4.57	.25	2.37	3.26	30.90			5	33	39	1.50		.18			
699.0	704.0	70497	5.0	.0	2E49	4.47	.21	2.42	3.78	29.20			5	33	39	.09		.18			
704.0	709.0	70498	5.0	.0	2E19	4.31	.24	1.30	2.55	16.00			5	33	39	.08		.18			
709.0	714.0	70499	5.0	.0	2E19	4.60	.24	2.65	4.65	23.80			5	33	39	.09		.18			
714.0	719.0	70500	5.0	.0	2E48	4.51	.18	3.04	4.63	18.80			5	31	36	.44		.14			
719.0	724.0	70501	5.0	.0	2E40	4.61	.15	2.81	5.14	12.20			5	31	36	.02		.14			
724.0	729.0	70502	5.0	.0	2E40	4.88	.10	4.05	7.86	17.80			5	31	36	.02		.14			
729.0	734.0	70503	5.0	.0	2C90	4.30	.20	2.96	7.26	13.70			5	31	36	.05		.14			
734.0	739.0	70504	5.0	.0	2A00	2.48	.17	.65	1.82	11.60			3	3	6	.24		.04			
739.0	744.0	70505	5.0	.0	2A00	2.65	.11	.80	1.84	13.20			3	3	6	.37		.04			
744.0	749.0	70506	5.0	.0	2B0	2.73	.04	1.13	2.36	14.20			3	3	6	.35		.04			
749.0	754.0	70507	5.0	.0	2B40	2.89	.03	1.37	4.42	15.60			3	3	6	.31		.04			
754.0	759.0	70508	5.0	.0	2B0	2.84	.07	.75	2.83	9.60			4	12	16	.42		.04			
759.0	764.0	70509	5.0	.0	2D37	3.23	.24	.74	3.64	13.30			4	12	16	.16		.04			
764.0	769.0	70510	5.0	.0	2D37	3.43	.35	1.35	4.73	18.30			4	12	16	.10		.04			
769.0	774.0	70511	5.0	.0	2A10	2.90	.22	.33	1.84	9.40			4	12	16	.28		.04			
774.0	779.0	70512	5.0	.0	2A1	2.63	.03	.98	1.17	5.40			4	12	16	.31		.04			

DDH: 66-11 UTM-N: 9199.3 UTM-E: 15199.7 UTM-ELEV: 4191.5 TOTAL DEPTH: 759.5 SECTION: 122+020
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

-----DEPTHS-----						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
551.0	556.0	70521	5.0	.0	2C39	3.36	.17	.94	1.43	19.30			6	13	20	.10		.06			
556.0	561.0	70522	5.0	.0	2C35	3.09	.17	1.11	2.23	23.30			6	13	20	.16		.06			
561.0	566.0	70523	5.0	.0	2D35	3.25	.05	2.19	4.35	26.80			4	13	18	.15		.04			
566.0	571.0	70524	5.0	.0	2C50	3.12	.16	.79	2.06	16.40			4	13	18	.21		.04			
571.0	576.0	70525	5.0	.0	2C50	3.37	.05	1.07	1.62	21.30			4	13	18	.16		.04			
576.0	581.0	70526	5.0	.0	0Q90	2.94	.10	1.16	3.28	18.90			4	13	18	.12		.04			
581.0	586.0	70527	5.0	.0	2C00	3.08	.06	1.12	1.93	18.80			5	7	12	.24		.02			
586.0	591.0	70528	5.0	.0	2C00	2.87	.14	.68	2.07	33.10			5	7	12	.34		.02			
591.0	596.0	70529	5.0	.0	2C90	2.94	.26	5.53	1.27	202.90			5	7	12	.22		.02			
596.0	601.0	70530	5.0	.0	2C00	3.01	.13	1.63	2.68	37.20			5	7	12	.25		.02			

DDH: 66-46 UTM-N: 9398.9 UTM-E: 14599.9 UTM-ELEV: 4161.1 TOTAL DEPTH: 800.0 SECTION: 118+000
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

-----DEPTHS-----						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
480.0	485.0	70804	5.0	.0	10E9(	2.96	.13	3.01	2.95	26.50			13	7	20	3.59		.24			
485.0	490.0	70805	5.0	.0	2D47	4.03	.19	4.38	5.65	67.70			13	7	20	9.16		.24			
490.0	495.0	70806	5.0	.0	2J84	3.94	.10	6.03	6.57	29.90			14	18	33	5.67		.35			
495.0	500.0	70807	5.0	.0	2E4*	3.86	.15	2.33	3.04	31.90			14	18	33	2.16		.35			
500.0	505.0	70808	5.0	.0	2E89	3.83	.22	1.82	1.69	28.50			14	18	33	.93		.35			
505.0	510.0	70809	5.0	.0	2G42	4.30	.30	5.32	4.76	56.40			14	18	33	3.59		.35			
510.0	515.0	70810	5.0	.0	2J89	3.85	.47	2.83	3.16	51.60			17	9	26	7.87		.35			
515.0	520.0	70811	5.0	.0	2J8*	4.20	.10	3.41	3.16	36.00			17	9	26	6.78		.35			
520.0	525.0	70812	5.0	.0	2G4	4.44	.13	6.85	6.76	90.30			17	9	26	23.70		.35			
525.0	530.0	70813	5.0	.0	2G4&	4.61	.14	5.76	6.33	75.50			17	9	26	23.07		.35			
530.0	535.0	70814	5.0	.0	2G4&	4.68	.11	8.10	7.30	103.40			4	21	25	26.06		.29			
535.0	540.0	70815	5.0	.0	2G4&	4.49	.10	5.68	6.28	77.20			4	21	25	23.15		.29			
540.0	545.0	70816	5.0	.0	2G4&	4.75	.13	4.38	5.14	59.40			4	21	25	17.72		.29			
545.0	550.0	70817	5.0	.0	2G4&	4.48	.13	3.20	4.63	41.90			4	21	25	7.91		.29			
550.0	555.0	70818	5.0	.0	2E48	3.29	.16	2.41	3.25	37.00			2	27	30	.18		.11			
555.0	560.0	70819	5.0	.0	2C3	3.28	.06	1.77	.19	69.10			2	27	30	.04		.11			
560.0	565.0	70820	5.0	.0	2C3	3.51	.02	.18	.14	11.90			2	27	30	.04		.11			
565.0	570.0	70821	5.0	.0	2E41	4.54	.12	2.50	1.83	27.70			2	27	30	.02		.11			
570.0	575.0	70822	5.0	.0	2E41	4.66	.10	2.33	1.91	25.80			4	36	40	.03		.12			
575.0	580.0	70823	5.0	.0	2E41	4.23	.33	1.36	2.61	17.90			4	36	40	.08		.12			
580.0	585.0	70824	5.0	.0	2E84	4.45	.21	2.37	2.95	20.70			4	36	40	.09		.12			
585.0	590.0	70825	5.0	.0	2E08	4.69	.20	.52	.67	2.70			4	36	40	.02		.12			
590.0	595.0	70826	5.0	.0	2E08	4.59	.18	1.16	2.33	4.20			5	31	36	.03		.13			
595.0	600.0	70827	5.0	.0	2E48	4.61	.14	4.06	8.82	13.90			5	31	36	.02		.13			
600.0	605.0	70828	5.0	.0	2E48	4.27	.44	2.11	2.75	20.60			5	31	36	.04		.13			
605.0	610.0	70829	5.0	.0	2F0	5.12	.11	2.65	6.52	5.80			5	31	36	.06		.13			
610.0	615.0	70830	5.0	.0	2F4	5.06	.08	3.45	6.99	9.40			3	35	38	.34		.04			
615.0	620.0	70831	5.0	.0	2F4	5.02	.07	4.88	7.65	18.10			3	35	38	.16		.04			
620.0	625.0	70832	5.0	.0	2F4	4.73	.05	5.35	9.58	16.80			3	35	38	.27		.04			
625.0	630.0	70833	5.0	.0	2E48	4.75	.20	1.13	4.85	2.50			3	35	38	.03		.04			
630.0	635.0	70834	5.0	.0	2E48	4.52	.23	1.82	3.44	4.90			7	32	39	.03		.17			
635.0	640.0	70835	5.0	.0	2E48	4.52	.24	2.44	4.31	7.80			7	32	39	.02		.17			
640.0	645.0	70836	5.0	.0	2E81	4.08	.26	.97	2.30	2.00			7	32	39	.02		.17			
645.0	650.0	70837	5.0	.0	2E81	4.09	.56	.64	2.23	4.10			7	32	39	.02		.17			
650.0	655.0	70838	5.0	.0	2E81	4.56	.43	2.38	4.82	8.20			10	25	36	.02		.07			
655.0	660.0	70839	5.0	.0	2F4	4.85	.07	4.95	9.64	11.10			10	25	36	.02		.07			
660.0	665.0	70840	5.0	.0	2F4(	3.92	.08	3.61	6.30	17.80			10	25	36	.08		.07			
665.0	670.0	70841	5.0	.0	2H48	4.05	.28	6.27	14.31	44.50			10	25	36	.06		.07			
670.0	675.0	70842	5.0	.0	2H48	3.11	.23	1.72	5.47	31.20			6	15	21	.14		.02			
675.0	680.0	70843	5.0	.0	2C7&	3.02	.15	.56	.26	8.60			6	15	21	.09		.02			
680.0	685.0	70844	5.0	.0	2A1	3.02	.03	.85	1.76	10.30			6	15	21	.10		.02			
685.0	690.0	70845	5.0	.0	2D4&	3.79	.04	3.88	12.15	28.50			6	15	21	.05		.02			
690.0	695.0	70846	5.0	.0	2D4&	4.01	.05	1.83	5.32	21.00			1	35	37	.04		.02			
695.0	700.0	70847	5.0	.0	2E44	5.08	.02	3.15	4.34	14.40			1	35	37	.01		.02			
700.0	705.0	70848	5.0	.0	2E44	4.50	.05	4.09	8.42	19.30			1	35	37	.02		.02			
705.0	710.0	70849	5.0	.0	2E4	5.20	.02	3.51	3.07	16.40			1	35	37	.01		.02			
710.0	715.0	70850	5.0	.0	2F1	3.44	.02	3.51	4.42	15.80			2	30	33	.01		.02			
715.0	720.0	70851	5.0	.0	2F1	3.65	.03	2.72	5.19	14.80			2	30	33	.02		.02			
720.0	725.0	70852	5.0	.0	2F1	3.59	.10	2.62	6.88	19.80			2	30	33	.11		.02			
725.0	730.0	70853	5.0	.0	2D4&	3.65	.09	4.12	10.21	29.00			2	30	33	.06		.02			
730.0	735.0	70854	5.0	.0	2D4&	3.42	.17	5.96	10.96	115.50			7	9	16	.05		.03			

DDH: 66-46 UTM-N: 9398.9 UTM-E: 14599.9 UTM-ELEV: 4161.1 TOTAL DEPTH: 800.0 SECTION: 118+000
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

-----DEPTHS-----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
735.0	740.0	70855	5.0	.0	2D48	2.92	.27	2.87	7.41	40.50			7	9	16	.16		.03			
740.0	745.0	70856	5.0	.0	2A97	3.18	.19	.84	2.52	20.80			7	9	16	.22		.03			
745.0	750.0	70857	5.0	.0	2C79	3.03	.22	.25	1.55	13.80			7	9	16	.33		.03			
750.0	755.0	70858	5.0	.0	2C79	2.99	.35	.04	.31	21.20			15	1	16	.29		.02			
755.0	760.0	70859	5.0	.0	2C79	2.97	.27	.60	1.27	23.10			15	1	16	.20		.02			

DDH: 66-47 UTM-N: 9599.8 UTM-E: 15199.8 UTM-ELEV: 4217.1 TOTAL DEPTH: 700.0 SECTION: 120+000
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

-----DEPTHS-----						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
590.0	595.0	70867	5.0	.0	2L40	2.90	.19	1.41	.10	219.90			3	4	7	.12		.05			
595.0	600.0	70868	5.0	.0	2L40	2.73	.09	.56	.09	49.00			3	4	7	.14		.05			
600.0	605.0	70869	5.0	.0	2L40	2.78	.02	.04	.09	1.20			3	4	7	.16		.05			
605.0	610.0	70870	5.0	.0	2D00	3.07	.12	1.75	3.53	14.40			3	4	7	.12		.05			
610.0	615.0	70871	5.0	.0	2D00	3.16	.31	2.50	4.41	32.20			5	7	12	.14		.04			
615.0	620.0	70872	5.0	.0	2B9&	3.00	.20	.96	1.57	27.00			5	7	12	.22		.04			

DDH: 66-49 UTM-N: 8799.3 UTM-E: 14399.5 UTM-ELEV: 4059.5 TOTAL DEPTH: 750.0 SECTION: 120+000
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

-----DEPTHS-----						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
555.0	560.0	70877	5.0	.0	2H43	3.22	.16	2.56	3.21	41.00			15	13	29	.19		.25			
560.0	565.0	70878	5.0	.0	2H43	4.87	.23	6.00	7.66	78.40			15	13	29	.17		.25			
565.0	570.0	70879	5.0	.0	2H49	4.47	.29	8.79	9.53	117.70			15	13	29	.10		.25			
570.0	575.0	70880	5.0	.0	2H49	4.71	.42	7.48	8.09	98.80			12	14	26	1.14		.36			
575.0	580.0	70881	5.0	.0	2D47	3.73	.18	3.84	4.04	59.10			12	14	26	1.84		.36			
580.0	585.0	70882	5.0	.0	2L14	3.05	.14	2.73	2.83	42.20			12	14	26	3.09		.36			
585.0	590.0	70883	5.0	.0	2H49	4.53	.27	7.08	9.26	100.30			12	14	26	.62		.36			
590.0	595.0	70884	5.0	.0	2G49	4.68	.20	4.57	6.88	41.80			5	20	25	7.31		.13			
595.0	600.0	70885	5.0	.0	2E10	5.07	.17	1.31	1.94	17.30			5	20	25	.34		.13			
600.0	605.0	70886	5.0	.0	2B49	2.76	.22	2.07	3.58	46.70			5	20	25	.26		.13			
605.0	610.0	70887	5.0	.0	2B49	2.99	.23	3.69	2.01	67.60			5	20	25	.31		.13			
610.0	615.0	70888	5.0	.0	2B0	2.76	.09	.72	1.97	15.10			9	20	30	.41		.10			
615.0	620.0	70889	5.0	.0	2B49	3.40	.30	2.14	3.50	37.90			9	20	30	.38		.10			
620.0	625.0	70890	5.0	.0	2E90	4.84	.47	1.40	1.31	21.90			9	20	30	.02		.10			
625.0	630.0	70891	5.0	.0	2E90	5.15	.42	2.82	1.16	21.60			9	20	30	.02		.10			
630.0	635.0	70892	5.0	.0	2E90	4.77	.42	3.93	3.77	26.50			5	34	40	.02		.17			
635.0	640.0	70893	5.0	.0	2E90	4.46	.24	2.64	5.06	20.60			5	34	40	.03		.17			
640.0	645.0	70894	5.0	.0	2F49	4.71	.46	5.28	4.63	35.90			5	34	40	.02		.17			
645.0	650.0	70895	5.0	.0	2F4	4.93	.12	4.30	7.12	24.60			5	34	40	.02		.17			
650.0	655.0	70896	5.0	.0	2A49	3.54	.24	2.24	4.61	21.10			5	10	16	.18		.05			
655.0	660.0	70897	5.0	.0	2A4	2.72	.05	1.09	3.23	23.70			5	10	16	.32		.05			
660.0	665.0	70898	5.0	.0	2A4	2.92	.08	1.25	3.13	34.80			5	10	16	.23		.05			
665.0	670.0	70899	5.0	.0	2D90	3.49	.28	2.03	4.72	51.10			5	10	16	.17		.05			
670.0	675.0	70900	5.0	.0	2D00	3.27	.19	1.57	3.11	32.10			5	5	11	.28		.08			
675.0	680.0	70901	5.0	.0	2A40	3.02	.10	2.47	2.51	53.40			5	5	11	.15		.08			
680.0	685.0	70902	5.0	.0	2A4	2.88	.10	1.26	3.19	29.20			5	5	11	.16		.08			

DDH: 66-52 UTM-N: 8996.9 UTM-E: 14199.1 UTM-ELEV: 4038.8 TOTAL DEPTH: 725.0 SECTION: 118+000
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

-----DEPTHS-----						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
515.0	520.0	70907	5.0	.0	2H49	4.48	.38	5.17	7.34	58.00			20	6	27	.19		.11			
520.0	525.0	70908	5.0	.0	2D49	4.05	.38	6.34	9.32	69.80			20	6	27	.17		.11			
525.0	530.0	70909	5.0	.0	2D0	2.59	.09	2.27	6.05	31.10			20	6	27	.15		.11			
530.0	535.0	70910	5.0	.0	2D40	3.93	.21	5.31	8.11	71.60			8	25	33	.17		.11			
535.0	540.0	70911	5.0	.0	2F4	4.67	.20	5.68	7.85	56.00			8	25	33	.10		.11			
540.0	545.0	70912	5.0	.0	2F4	4.78	.17	6.42	8.14	64.80			8	25	33	1.67		.11			
545.0	550.0	70913	5.0	.0	2F4	4.72	.07	6.71	9.67	62.30			8	25	33	.07		.11			
550.0	555.0	70914	5.0	.0	2F4	5.14	.16	7.62	7.49	71.20			2	30	33	.09		.08			
555.0	560.0	70915	5.0	.0	2F4	5.30	.07	7.68	9.39	55.70			2	30	33	.05		.08			
560.0	565.0	70916	5.0	.0	2F4	4.88	.10	7.25	9.12	53.50			2	30	33	.08		.08			
565.0	570.0	70917	5.0	.0	2G42	3.46	.26	6.60	7.80	52.60			2	30	33	12.13		.08			
570.0	575.0	70918	5.0	.0	2F4	5.20	.06	6.84	9.79	54.10			4	24	28	.16		.11			
575.0	580.0	70919	5.0	.0	2F40	4.72	.10	7.85	8.81	72.10			4	24	28	6.34		.11			
580.0	585.0	70920	5.0	.0	2F46	4.90	.16	10.28	12.02	114.00			4	24	28	4.67		.11			
585.0	590.0	70921	5.0	.0	2G42	5.00	.09	8.26	9.06	95.40			4	24	28	19.48		.11			
590.0	595.0	70922	5.0	.0	2G42	4.57	.29	4.87	4.74	53.70			4	30	35	14.28		.09			
595.0	600.0	70923	5.0	.0	2F40	5.25	.17	3.72	5.23	39.30			4	30	35	.25		.09			
600.0	605.0	70924	5.0	.0	2F40	4.79	.08	3.95	7.13	38.00			4	30	35	.13		.09			
605.0	610.0	70925	5.0	.0	2F40	4.63	.08	5.15	7.43	45.80			4	30	35	.07		.09			
610.0	615.0	70926	5.0	.0	2A00	2.91	.04	.94	2.31	17.20			3	2	6	.50		.04			
615.0	620.0	70927	5.0	.0	2B4	3.11	.11	1.72	3.32	34.40			3	2	6	.35		.04			
620.0	625.0	70928	5.0	.0	2B40	3.04	.08	1.18	2.80	24.90			3	2	6	.33		.04			
625.0	630.0	70929	5.0	.0	2A00	2.96	.10	.36	.56	9.90			3	2	6	.21		.04			
630.0	635.0	70930	5.0	.0	1D4	2.64	.20	.23	.13	65.80			3	2	5	.14		.07			
635.0	639.0	70931	4.0	.0	1D4	2.79	.05	.02	.22	3.40			3	2	5	.19		.07			

PAGE: 17

---DEPTHS---			S.G.	PULP	Cu	Pb	Zn	Ag(AA)	Ag(FA)	Au(FA)	---ASSAYS---											
FROM	TO	SAMPLE NO.									INT.	REC.	ROCK UNIT	%	%	%	g/mT	g/mT	g/mT	Po %	Py %	TOT Fe
269.0	274.0	70160	5.0	.0	****	.50	.25	.30														
274.0	278.8	70161	4.8	.0	****	.50	.34	2.50	3.45	27.10												
278.8	283.6	70162	4.8	.0	****	.50	.35	6.80	7.70	110.70												
283.6	288.5	70163	4.9	.0	****	.50	.32	6.05	6.30	87.40												
288.5	293.2	70164	4.7	.0	****	.50	.32	.60	1.60	56.60												
293.2	297.8	70165	4.6	.0	****	.50	.11	.50	1.50	17.10												
297.8	302.0	70166	4.2	.0	****	.50	.12	.40	.10	6.80												
302.0	307.0	70167	5.0	.0	****	.50	.16	3.10	4.20	56.60												
307.0	312.0	70168	5.0	.0	****	.50																
312.0	317.0	70169	5.0	.0	****	.50	.52	1.10	1.15	10.30												
317.0	322.0	70170	5.0	.0	****	.50	.23	3.90	5.50	15.40												
322.0	327.0	70171	5.0	.0	****	.50	.53	2.00	2.20	15.40												
327.0	332.0	70172	5.0	.0	****	.50	.21	3.70	2.70	30.90												
332.0	337.0	70173	5.0	.0	****	.50	.27	3.60	5.10	36.00												
337.0	342.0	70174	5.0	.0	****	.50	.20	4.25	7.35	85.70												
342.0	347.0	70175	5.0	.0	****	.50	.30	3.85	5.70	51.40												
347.0	352.0	70176	5.0	.0	****	.50	.22	3.30	6.40	48.00												
352.0	357.0	70177	5.0	.0	****	.50	.14	3.00	7.60	44.60												
357.0	362.0	70178	5.0	.0	****	.50	.16	3.45	8.45	66.90												
362.0	367.0	70179	5.0	.0	****	.50	.13	.65	.20	13.70												
367.0	372.0	70180	5.0	.0	****	.50	.14	1.10	.20	10.30												
372.0	377.0	70181	5.0	.0	****	.50	.45	2.50	3.10	27.40												
377.0	382.0	70182	5.0	.0	****	.50	.31	1.90	2.20	20.60												
382.0	387.0	70183	5.0	.0	****	.50	.52	2.15	2.60	24.00												
387.0	392.0	70184	5.0	.0	****	.50	.35	4.10	3.40	37.70												
392.0	397.0	70185	5.0	.0	****	.50	.33	2.70	2.90	24.00												
397.0	402.0	70186	5.0	.0	****	.50																

PAGE: 19

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	---ASSAYS---													
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %
243.0	248.0	70262	5.0	.0	****	.50	.22	.01	.01	11.00										
248.0	253.0	70263	5.0	.0	****	.50	.07	.01	2.40	1.40										
253.0	258.0	70264	5.0	.0	****	.50	.07	2.10	4.60	70.00										
306.0	311.0	70267	5.0	.0	****	.50	.15	3.20	7.00	19.20										
311.0	316.0	70268	5.0	.0	****	.50	.07	2.60	4.50	6.90										
316.0	321.0	70269	5.0	.0	****	.50	.18	.60	2.00	.10										
321.0	326.0	70270	5.0	.0	****	.50	.30	2.30	4.30	6.90										
326.0	331.0	70271	5.0	.0	****	4.29	.90	1.50	2.30	.10										
331.0	336.0	70272	5.0	.0	****	.50	.22	2.10	5.10	.10										
336.0	341.0	70273	5.0	.0	****	.50	.30	.50	2.60	.10										
341.0	346.0	70274	5.0	.0	****	.50	.27	.70	5.00	.10										
346.0	351.0	70275	5.0	.0	****	.50	.21	2.90	5.30											
351.0	356.0	70276	5.0	.0	****	.50	.33	2.70	3.50	28.80										
356.0	361.0	70277	5.0	.0	****	.50	.30	4.60	7.30	65.80										
361.0	366.0	70278	5.0	.0	****	.50	.16	5.20	8.10	76.80										
366.0	371.0	70279	5.0	.0	****	.50	.07	1.90	2.50	11.00										
371.0	376.0	70280	5.0	.0	****	.50	.33	.20	2.10	2.70										
376.0	381.0	70281	5.0	.0	****	.50	.42	.01	2.10	1.40										
381.0	386.0	70282	5.0	.0	****	.50	.22	.01	2.30	.10										
386.0	391.0	70283	5.0	.0	****	.50	.22	.01	2.40	2.70										
391.0	396.0	70284	5.0	.0	****	.50	.01	1.60	.70	2.70										
396.0	401.0	70285	5.0	.0	****	.50	.01	2.50	3.30	6.90										
401.0	406.0	70286	5.0	.0	****	.50	.15	1.40	2.00	4.10										
406.0	411.0	70287	5.0	.0	****	.50	.07	1.40	4.50	2.70										
411.0	416.0	70288	5.0	.0	****	.50	.07	2.40	4.10	2.70										
416.0	421.0	70289	5.0	.0	****	.50	.15	.01	4.40	.10										
421.0	426.0	70290	5.0	.0	****	.50	.16	.20	2.50	.10										
426.0	431.0	70291	5.0	.0	****	.50	.22	.40	2.20	2.70										
431.0	436.0	70292	5.0	.0	****	.50	.07	2.40	4.10	5.50										
436.0	441.0	70293	5.0	.																

PAGE: 20

[illegible]

DDH: 66008 UTM-N: 9799.6 UTM-E: 13799.0 UTM-ELEV: 4189.5 TOTAL DEPTH: 700.0 SECTION:
RFE: RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	---ASSAYS---													
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %
270.0	275.0	70405	5.0	.0	****	.50	.21	.01	.01	15.10										
275.0	280.0	70406	5.0	.0	****	.50	.07	.20	.01	5.50										
280.0	285.0	70407	5.0	.0	****	.50	.07	.01	.50	4.10										
285.0	290.0	70408	5.0	.0	****	.50	.07	2.60	8.10	22.00										
290.0	295.0	70409	5.0	.0	****	.50	.07	4.20	6.70	60.40										
295.0	300.0	70410	5.0	.0	****	.50	.18	2.90	5.00	30.20										
300.0	305.0	70411	5.0	.0	****	.50	.67	4.90	5.40	93.30										
305.0	310.0	70412	5.0	.0	****	.50	.16	4.40	5.30	65.80										
310.0	315.0	70413	5.0	.0	****	.50	.15	4.90	6.90	32.90										
315.0	320.0	70414	5.0	.0	****	.50	.16	4.80	6.20	71.30										
320.0	325.0	70415	5.0	.0	****	.50	.18	5.80	6.00	79.60										
325.0	330.0	70416	5.0	.0	****	.50	.20	7.40	7.00	91.90										
330.0	335.0	70417	5.0	.0	****	.50	.37	5.50	7.10	79.60										
335.0	340.0	70418	5.0	.0	****	.50	.10	7.70	7.20	119.30										
340.0	345.0	70419	5.0	.0	****	.50	.22	4.90	6.20	74.10										
345.0	350.0	70420	5.0	.0	****	.50	.24	3.30	6.90	72.70										
350.0	355.0	70421	5.0	.0	****	.50	.27	4.60	7.70	71.30										
355.0	360.0	70422	5.0	.0	****	.50	.18	5.10	6.80	68.60										
360.0	365.0	70423	5.0	.0	****	.50	.22	4.40	4.40	42.50										
365.0	370.0	70424	5.0	.0	****	.50	.15	7.50	7.10	79.60										
370.0	375.0	70425	5.0	.0	****	.50	.30	.20	5.30	17.80										
375.0	380.0	70426	5.0	.0	****	.50	.07	4.70	7.30	39.80										
380.0	385.0	70427	5.0	.0	****	.50	.07	5.40	7.30	72.70										
385.0	390.0	70428	5.0	.0	****	.50	.15	3.40	4.50	37.00										
390.0	395.0	70429	5.0	.0	****	.50	.15	2.30	1.90	20.60										
395.0	400.0	70430	5.0	.0	****	.50	.43	.70	1.30	13.70										
400.0	405.0	70431	5.0	.0	****	.50	.25	3.90	6.50	23.30										
405.0	410.0	70432	5.0	.0	****	.50	.60	2.70	4.50	19.20										
410.0	415.0	70433	5.0	.0	****	.50	.21	4.10	6.10	26.10										
415.0	420.0	70434	5.0	.0	****	.50	.46	2.70	4.10	17.80										
420.0	425.0	70435	5.0	.0	****	.50	.37	3.00	2.80	22.00										
425.0	430.0	70436	5.0	.0	****	.50	.15	3.80	5.30	26.10										
430.0	435.0	70437	5.0	.0	****	.50	.61	1.50	2.00	13.70										
435.0	440.0	70438	5.0	.0	****	.50	.16	3.30	5.20	16.50										
440.0	445.0	70439	5.0	.0	****	.50	.15	3.80	6.60	17.80										
445.0	450.0	70440	5.0	.0	****	.50	.19	4.50	6.30	26.10										
450.0	455.0	70441	5.0	.0	****	.50	.75	2.80	3.90	15.10										
455.0	460.0	70442	5.0	.0	****	.50	.15	2.80	5.00	15.10										
460.0	465.0	70443	5.0	.0	****	.50	.07	4.20	5.70	16.50										
465.0	470.0	70444	5.0	.0	****	.50	.30	2.50	4.10	8.20										
470.0	475.0	70445	5.0	.0	****	.50	.15	3.30	5.20	13.70										
475.0	480.0	70446	5.0	.0	****	.50	.22	3.90	6.70	20.60										
480.0	485.0	70447	5.0	.0	****	.50	.21	4.80	5.10	20.60										
485.0	490.0	70448	5.0	.0	****	.50	.07	4.70	6.40	61.70										
490.0	495.0	70449	5.0	.0	****	.50	.28	3.60	5.10	13.70										
495.0	500.0	70450	5.0	.0	****	.50	.42	3.10	4.10	22.00										
500.0	505.0	70451	5.0	.0	****	.50	.28	6.90	9.00	87.80										
505.0	510.0	70452	5.0	.0	****	.50	.07	6.40	10.90											
510.0	515.0	70453	5.0	.0	****	.50	.01	7.30	11.70											
515.0	520.0	70454	5.0	.0	****	.50	.60	2.00	3.60	13.70										
520.0	525.0	70455	5.0	.0	****	.50	.15	2.50	4.30	7.50										

PAGE: 22

[illegible]

PAGE: 23

[illegible]

DDH: 66022 UTM-N: 9797.9 UTM-E: 14199.0 UTM-ELEV: 4124.1 TOTAL DEPTH: 430.5 SECTION:
 RFE: RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----						-----ASSAYS-----																	
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.		
215.0	220.0	70556	5.0	.0	****	3.10	.18	.23	.76	10.00			5	15	21	.39		.12					
220.0	225.0	70557	5.0	.0	****	3.79	.06	.64	3.30	15.00			5	15	21	.86		.12					
225.0	230.0	70558	5.0	.0	****	3.90	.22	3.24	3.39	66.00			5	15	21	9.37		.12					
230.0	235.0	70559	5.0	.0	****	3.65	.24	2.48	2.65	68.00			5	15	21	6.46		.12					
235.0	240.0	70560	5.0	.0	****	3.59	.38	4.99	3.62	126.00			6	8	15	7.11		.13					
240.0	245.0	70561	5.0	.0	****	3.09	.22	1.52	.56	86.00			6	8	15	3.19		.13					
245.0	255.0	70562	10.0	.0	****	3.32	.41	3.04	2.38	75.00			6	8	15	6.43		.13					
255.0	260.0	70563	5.0	.0	****	4.19	.24	4.12	3.79	76.00			5	18	23	13.18		.20					
260.0	265.0	70564	5.0	.0	****	4.76	.19	3.14	3.82	42.00			5	18	23	9.14		.20					
265.0	270.0	70565	5.0	.0	****	4.51	.08	4.09	5.26	63.00			5	18	23	33.17		.20					
270.0	275.0	70566	5.0	.0	****	4.78	.08	6.52	7.19	112.00			5	18	23	36.66		.20					
275.0	280.0	70567	5.0	.0	****	4.92	.08	5.00	5.71	66.00			4	25	29	24.12		.10					
280.0	285.0	70568	5.0	.0	****	4.80	.10	4.93	6.93	68.00			4	25	29	28.49		.10					
285.0	290.0	70569	5.0	.0	****	4.63	.18	2.56	4.76	42.00			4	25	29	15.67		.10					
290.0	295.0	70570	5.0	.0	****	4.85	.19	2.07	1.97	27.00			4	25	29	2.59		.10					
295.0	300.0	70571	5.0	.0	****	4.65	.02	3.54	7.56	35.00			2	33	36	27.63		.02					
300.0	305.0	70572	5.0	.0	****	4.81	.16	1.38	1.06	21.00			2	33	36	1.22		.02					
305.0	310.0	70573	5.0	.0	****	4.50	.18	1.02	.67	14.00			2	33	36	.04		.02					
310.0	315.0	70574	5.0	.0	****	4.45	.12	.59	.41	10.00			2	33	36	.05		.02					
315.0	320.0	70575	5.0	.0	****	4.81	.22	3.20	4.85	17.00			6	31	37	.05		.12					
320.0	325.0	70576	5.0	.0	****	4.49	.19	2.55	7.10	10.00			6	31	37	.03		.12					
325.0	330.0	70577	5.0	.0	****	4.42	.38	1.87	4.42	7.00			6	31	37	.05		.12					
330.0	335.0	70578	5.0	.0	****	4.27	.16	1.61	2.15	6.00			6	31	37	.12		.12					
335.0	340.0	70579	5.0	.0	****	4.44	.17	3.64	5.67	6.00			7	29	36	.02		.19					
340.0	345.0	70580	5.0	.0	****	4.52	.24	1.42	3.26	4.00			7	29	36	.01		.19					
345.0	350.0	70581	5.0	.0	****	4.60	.27	9.40	15.15	13.00			7	29	36	.02		.19					
350.0	355.0	70582	5.0	.0	****	4.30	.24	.70	2.21	3.00			7	29	36	.03		.19					
355.0	360.0	70583	5.0	.0	****	4.73	.09	4.67	9.63	21.00			6	30	36	.03		.11					
360.0	365.0	70584	5.0	.0	****	4.50	.42	1.20	1.21	21.90						.03							
365.0	370.0	70585	5.0	.0	****	4.50	.24	2.40	3.65	30.20						.03							
370.0	375.0	70586	5.0	.0	****	4.13	.49	.39	1.70	8.00			6	30	36	.03		.11					
375.0	380.0	70587	5.0	.0	****	4.44	.52	.46	1.54	8.00			7	33	40	.02		.12					
380.0	385.0	70588	5.0	.0	****	4.23	.59	.58	1.10	10.00			7	33	40	.02		.12					
385.0	390.0	70589	5.0	.0	****	4.60	.58	.19	1.24	10.00			7	33	40	.05		.12					
390.0	395.0	70590	5.0	.0	****	4.20	.19	.17	1.54	6.00			7	33	40	.04		.12					
395.0	400.0	70591	5.0	.0	****	4.23	.15	1.01	3.03	11.00			6	31	37	.02		.11					
400.0	405.0	70592	5.0	.0	****	4.27	.19	1.20	2.80	5.50						.02							
405.0	410.0	70593	5.0	.0	****	4.30	.25	1.10	2.92	9.00			6	31	37	.02		.11					
410.0	420.0	70594	10.0	.0	****	4.15	.15	2.99	5.43	8.20						.02							
420.0	425.0	70595	5.0	.0	****	4.15		4.40	8.27	21.90						.02							
425.0	430.5	70596	5.5	.0	****	4.15		4.80	5.19	26.00						.02							

```
DDH: 66026      UTM-N:  9399.9      UTM-E: 13397.3      UTM-ELEV: 4150.1      TOTAL DEPTH: 500.0      SECTION:
RFE:           RFE DIR:    0 PLUNGE ANGLES:    0      0 DHD CALC:    1 SS CALC:    0
```

[illegible]

DDH: 66030 UTM-N: 9793.0 UTM-E: 14536.3 UTM-ELEV: 4124.7 TOTAL DEPTH: 526.0 SECTION:
 RFE: RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
215.0	220.0	70621	5.0	.0	****	2.80	.09	1.02	1.43	19.20			7	9	16	1.21		.06			
220.0	225.0	70622	5.0	.0	****	3.06	.18	1.10	6.11	22.70			7	9	16	.64		.06			
225.0	230.0	70623	5.0	.0	****	3.48	.29	4.44	7.31	48.30			7	9	16	.21		.06			
230.0	235.0	70624	5.0	.0	****	3.31	.75	.23	.96	16.00			7	9	16	.17		.06			
235.0	240.0	70625	5.0	.0	****	2.87	.26	.22	.48	9.30			4	6	11	.11		.04			
240.0	245.0	70626	5.0	.0	****	2.75	.01	.04	.06	.90			4	6	11	.14		.04			
245.0	250.0	70627	5.0	.0	****	2.75	.24	.38	.18	18.00			4	6	11	.19		.04			
250.0	255.0	70628	5.0	.0	****	3.35	.36	1.77	1.76	29.20			4	6	11	.07		.04			
255.0	260.0	70629	5.0	.0	****	2.81	.22	1.06	.24	17.30			3	15	18	.12		.03			
260.0	265.0	70630	5.0	.0	****	3.19	.16	.52	1.02	9.90			3	15	18	.09		.03			
265.0	270.0	70631	5.0	.0	****	3.90	.15	.45	1.50	4.80			3	15	18	.08		.03			
270.0	275.0	70632	5.0	.0	****	4.01	.17	1.57	2.45	13.40			3	15	18	.06		.03			
275.0	280.0	70633	5.0	.0	****	3.91	.09	3.00	5.25	20.30			3	7	11	.13		.06			
280.0	285.0	70634	5.0	.0	****	3.02	.10	2.71	6.74	21.00			3	7	11	.18		.06			
285.0	290.0	70635	5.0	.0	****	2.75	.06	.32	.34	8.40			3	7	11	.22		.06			
290.0	295.0	70636	5.0	.0	****	2.79	.03	.21	.27	5.00			3	7	11	.27		.06			
295.0	300.0	70637	5.0	.0	****	3.24	.14	2.87	4.41	26.30			3	16	19	.21		.05			
300.0	305.0	70638	5.0	.0	****	3.54	.17	1.90	4.46	19.50			3	16	19	.10		.05			
305.0	310.0	70639	5.0	.0	****	3.66	.10	2.20	7.35	13.20			3	16	19	.09		.05			
310.0	315.0	70640	5.0	.0	****	3.64	.09	1.99	7.16	13.30			3	16	19	.11		.05			
315.0	320.0	70641	5.0	.0	****	3.67	.04	2.91	5.33	19.60			2	20	22	.14		.02			
320.0	325.0	70642	5.0	.0	****	3.55	.03	3.57	5.80	31.00			2	20	22	.14		.02			
325.0	330.0	70643	5.0	.0	****	3.78	.02	1.48	5.07	14.00			2	20	22	.13		.02			
330.0	335.0	70644	5.0	.0	****	3.67	.02	3.96	6.44	27.00			2	20	22	.19		.02			
335.0	340.0	70645	5.0	.0	****	3.35	.04	1.22	6.73	14.80			2	21	23	.27		.02			
340.0	345.0	70646	5.0	.0	****	4.08	.05	1.82	4.64	16.40			2	21	23	.11		.02			
345.0	350.0	70647	5.0	.0	****	3.83	.02	2.15	5.48	14.60			2	21	23	.10		.02			
350.0	355.0	70648	5.0	.0	****	3.24	.05	2.89	5.86	24.70			2	21	23	.15		.02			
355.0	360.0	70649	5.0	.0	****	3.44	.06	4.37	8.09	33.20			2	15	18	.17		.01			
360.0	365.0	70650	5.0	.0	****	3.40	.05	6.36	12.33	35.20			2	15	18	.12		.01			
365.0	370.0	70651	5.0	.0	****	3.38	.04	.54	2.08	15.50			2	15	18	.15		.01			
370.0	375.0	70652	5.0	.0	****	3.60	.04	.50	2.80	11.50			2	15	18	.11		.01			
375.0	380.0	70653	5.0	.0	****	3.51	.06	3.02	10.11	16.40			2	16	18	.17		.01			
380.0	385.0	70654	5.0	.0	****	3.75	.03	4.26	12.32	18.40			2	16	18	.16		.01			
385.0	390.0	70655	5.0	.0	****	3.35	.06	1.38	2.46	17.50			2	16	18	.20		.01			
390.0	395.0	70656	5.0	.0	****	3.02	.04	.50	.58	8.30			2	16	18	.23		.01			
395.0	400.0	70657	5.0	.0	****	3.10		.08	.35	7.20			1	24	26	.01		.01			
400.0	405.0	70658	5.0	.0	****	3.02	.04	.16	1.11	6.20			1	24	26	.18		.01			
405.0	410.0	70659	5.0	.0	****	3.02	.05	.98	4.93	14.40			1	24	26	.07		.01			
410.0	415.0	70660	5.0	.0	****	3.43	.08	.54	1.61	11.60			1	24	26	.19		.01			
415.0	420.0	70661	5.0	.0	****	3.38	.03	1.78	2.78	18.30			2	14	17	.17		.02			
420.0	425.0	70662	5.0	.0	****	3.31	.02	2.26	6.39	28.60			2	14	17	.20		.02			
425.0	430.0	70663	5.0	.0	****	3.11	.03	1.86	5.38	24.10			2	14	17	.22		.02			
430.0	435.0	70664	5.0	.0	****	3.39	.04	2.20	4.03	25.00			2	14	17	.20		.02			
435.0	440.0	70665	5.0	.0	****	3.38	.04	.56	1.88	11.50			2	29	32	.20		.02			
440.0	445.0	70666	5.0	.0	****	4.64	.01	2.68	6.81	21.80			2	29	32	.06		.02			
445.0	450.0	70667	5.0	.0	****	5.09		6.10	8.36	34.00			2	29	32	.01		.02			
450.0	455.0	70668	5.0	.0	****	4.93		5.08	10.41	37.50			2	29	32	.01		.02			
455.0	460.0	70669	5.0	.0	****	4.63	.01	3.13	12.09	22.10			2	33	35	.02		.01			
460.0	465.0	70670	5.0	.0	****	5.04	.02	5.15	14.81	35.50			2	33	35	.02		.01			
465.0	470.0	70671	5.0	.0	****	4.99		1.20	3.09	13.00			2	33	35	.01		.01			

DDH: 66030 UTM-N: 9793.0 UTM-E: 14536.3 UTM-ELEV: 4124.7 TOTAL DEPTH: 526.0 SECTION:
 RFE: RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS----						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
470.0	475.0	70672	5.0	.0	****	4.85	.09	4.63	9.85	42.80			2	33	35	.02		.01			
475.0	480.0	70673	5.0	.0	****	2.98	.23	.84	4.42	22.70			4	4	8	.15		.06			
480.0	485.0	70674	5.0	.0	****	2.69	.07	.68	.06	15.80			4	4	8	.23		.06			
485.0	490.0	70675	5.0	.0	****	2.74	.06	.38	.01	11.90			4	4	8	.17		.06			
490.0	495.0	70676	5.0	.0	****	2.84	.14	2.06	.01	51.00			4	4	8	.14		.06			
495.0	500.0	70677	5.0	.0	****	2.75	.01	.06	.01	1.70			5	5	10	.16		.03			
500.0	505.0	70678	5.0	.0	****	3.06	.14	.68	2.16	19.70			5	5	10	.15		.03			
505.0	510.0	70679	5.0	.0	****	3.10	.17	1.58	6.42	20.00			5	5	10	.21		.03			
510.0	515.0	70680	5.0	.0	****	3.22	.14	2.93	7.54	34.20			5	5	10	.19		.03			
515.0	520.0	70681	5.0	.0	****	3.21	.06	4.93	9.78	45.30			6	5	11	.21		.02			
520.0	526.0	70682	6.0	.0	****	3.22	.12	1.98	6.13	32.90			6	5	11	.16		.02			

DDH: 66031 UTM-N: 9399.6 UTM-E: 13797.3 UTM-ELEV: 4128.0 TOTAL DEPTH: 500.0 SECTION:
 RFE: RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
385.0	390.0	70687	5.0	.0	****	2.63	.11	.61	1.05	8.00			4	3	8	.17		.06			
390.0	395.0	70688	5.0	.0	****	2.70	.11	1.07	.81	14.00			4	3	8	.19		.06			
395.0	400.0	70689	5.0	.0	****	2.61	.07	1.68	2.17	13.00			4	3	8	.33		.06			
400.0	405.0	70690	5.0	.0	****	3.59	.05	3.12	5.58	30.00			9	20	30	.08		.12			
405.0	410.0	70691	5.0	.0	****	4.18	.10	3.35	6.35	43.00			9	20	30	3.37		.12			
410.0	416.0	70692	6.0	.0	****	4.19	.13	4.91	6.97	75.00			9	20	30	7.07		.12			
416.0	423.0	70693	7.0	.0	****	4.29	.24	5.47	7.80	76.00			9	20	30	3.55		.12			
423.0	427.0	70694	4.0	.0	****	4.10	.35	5.90	8.46	86.00			22	11	33	.29		.13			
427.0	430.0	70695	3.0	.0	****	4.20	.27	8.63	9.97	100.00			22	11	33	.19		.13			
430.0	436.0	70696	6.0	.0	****	3.94	.29	7.49	7.92	76.00			22	11	33	.09		.13			
436.0	440.0	70697	4.0	.0	****	3.78	.25	7.10	7.80	66.00			22	11	33	.27		.13			
440.0	446.0	70698	6.0	.0	****	4.67	.11	6.57	6.81	80.00			6	29	36	1.31		.22			
446.0	450.0	70699	4.0	.0	****	4.44	.18	4.53	7.08	53.00			6	29	36	5.13		.22			
450.0	456.0	70700	6.0	.0	****	4.83	.25	5.59	5.83	51.00			6	29	36	.09		.22			
456.0	462.0	70701	6.0	.0	****	4.69	.28	5.25	5.98	43.00			5	28	34	.04		.17			
462.0	465.0	70702	3.0	.0	****	4.71	.17	6.33	6.97	73.00			5	28	34	4.65		.17			
465.0	471.0	70703	6.0	.0	****	4.81	.12	5.75	7.40	60.00			5	28	34	13.94		.17			
471.0	476.0	70704	5.0	.0	****	4.70	.06	5.43	8.15	43.00			5	28	34	.18		.17			
476.0	482.0	70705	6.0	.0	****	4.43	.28	4.54	6.26	57.00			16	7	24	.13		.04			
482.0	490.0	70706	8.0	.0	****	2.71	.06	1.95	2.47	39.00			16	7	24	.15		.04			
490.0	492.0	70707	2.0	.0	****	2.61	.01	.78	1.35	17.00			16	7	24	.05		.04			

DDH: 66033 UTM-N: 9399.3 UTM-E: 14197.3 UTM-ELEV: 4078.6 TOTAL DEPTH: 461.5 SECTION:
 RFE: RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS----						-----ASSAYS-----																	
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.		
310.0	315.0	70714	5.0	.0	****	3.20	.12	.93	1.22	19.00			11	10	21	.14		.05					
315.0	320.0	70715	5.0	.0	****	3.21	.26	.29	.12	5.00			11	10	21	.07		.05					
320.0	325.0	70716	5.0	.0	****	3.15	.29	.16	.06	5.00			11	10	21	.08		.05					
325.0	330.0	70717	5.0	.0	****	3.35	.26	2.82	4.98	36.50			11	10	21	.16		.05					
330.0	335.0	70718	5.0	.0	****	4.16	.33	6.61	9.17	77.00			14	10	25	.08		.14					
335.0	340.0	70719	5.0	.0	****	4.04	.31	5.38	8.61	73.00			14	10	25	1.84		.14					
340.0	345.0	70720	5.0	.0	****	3.59	.29	3.40	5.69	65.00			14	10	25	1.48		.14					
345.0	350.0	70721	5.0	.0	****	2.92	.06	1.93	4.62	33.50			14	10	25	.12		.14					
350.0	355.0	70722	5.0	.0	****	3.37	.13	4.51	8.03	57.00			6	19	25	.20		.13					
355.0	360.0	70723	5.0	.0	****	5.26	.06	7.05	11.69	74.50			6	19	25	3.30		.13					
360.0	365.0	70724	5.0	.0	****	4.51	.22	7.72	6.62	106.00			6	19	25	15.15		.13					
365.0	370.0	70725	5.0	.0	****	4.70	.12	5.67	7.58	61.00			6	19	25	17.70		.13					
370.0	375.0	70726	5.0	.0	****	4.78	.21	2.94	4.91	31.00			3	30	33	7.18		.08					
375.0	380.0	70727	5.0	.0	****	4.71	.07	3.96	6.64	42.00			3	30	33	30.05		.08					
380.0	385.0	70728	5.0	.0	****	4.63	.24	4.87	4.12	48.00			3	30	33	4.13		.08					
385.0	390.0	70729	5.0	.0	****	4.73	.30	2.58	2.60	37.00			3	30	33	.08		.08					
390.0	395.0	70730	5.0	.0	****	4.40	.31	6.75	8.06	48.00			5	30	35	.06		.10					
395.0	400.0	70731	5.0	.0	****	4.76	.25	3.67	3.44	42.00			5	30	35	.08		.10					
400.0	405.0	70732	5.0	.0	****	4.59	.18	5.11	4.84	52.00			5	30	35	4.75		.10					
405.0	410.0	70733	5.0	.0	****	4.57	.18	4.83	5.08	37.00			5	30	35	14.36		.10					
410.0	415.0	70734	5.0	.0	****	4.43	.19	1.98	2.25	21.00			3	30	33	2.38		.06					
415.0	420.0	70735	5.0	.0	****	4.59	.07	4.67	7.17	52.00			3	30	33	27.16		.06					
420.0	425.0	70736	5.0	.0	****	4.36	.19	2.61	3.82	21.00			3	30	33	.13		.06					
425.0	430.0	70737	5.0	.0	****	4.75	.25	5.20	11.39	30.00			3	30	33	.03		.06					
430.0	435.0	70738	5.0	.0	****	4.48	.58	1.64	1.56	12.00			3	38	41	.12		.06					
435.0	440.0	70739	5.0	.0	****	4.61	.33	.89	1.13	8.00			3	38	41	.05		.06					
440.0	445.0	70740	5.0	.0	****	5.10	.32	.59	2.07	8.00			3	38	41	.03		.06					
445.0	450.0	70741	5.0	.0	****	4.34	.54	1.42	1.88	11.00			3	38	41	.08		.06					
450.0	455.0	70742	5.0	.0	****	4.58	.33	1.65	3.05	9.00			3	36	39	.02		.05					
455.0	461.5	70743	6.5	.0	****	4.69	.14	3.51	6.33	17.00			3	36	39	.02		.05					

DDH: 66057 UTM-N: 9919.0 UTM-E: 14690.0 UTM-ELEV: 4207.8 TOTAL DEPTH: 600.0 SECTION:
 RFE: RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
295.0	300.0	70957	5.0	.0	****	3.81	.03	.91	3.49	21.90			7	11	19	.10		.06			
300.0	305.0	70958	5.0	.0	****	3.81	.08	1.50	4.23	16.30			7	11	19	.10		.06			
305.0	310.0	70959	5.0	.0	****	3.32	.32	3.06	4.02	40.10			7	11	19	.08		.06			
360.0	365.0	70961	5.0	.0	****	2.77	.18	1.30	.16	34.00			3	18	21	.13		.04			
365.0	370.0	70962	5.0	.0	****	3.45	.33	2.21	.62	40.40			3	18	21	.09		.04			
370.0	375.0	70963	5.0	.0	****	3.04	.06	.76	.50	9.00			3	18	21	.04		.04			
375.0	380.0	70964	5.0	.0	****	3.20	.03	.50	1.68	20.00			3	18	21	.15		.04			
380.0	385.0	70965	5.0	.0	****	3.23	.11	1.54	3.45	16.20			4	7	11	.15		.05			
385.0	390.0	70966	5.0	.0	****	3.12	.10	1.68	4.37	22.20			4	7	11	.17		.05			
390.0	395.0	70967	5.0	.0	****	2.66	.14	1.06	.36	24.00			4	7	11	.10		.05			
395.0	400.0	70968	5.0	.0	****	3.19	.25	1.14	2.48	19.30			4	7	11	.11		.05			
400.0	405.0	70969	5.0	.0	****	3.26	.23	1.88	4.62	24.30			5	11	16	.06		.05			
405.0	410.0	70970	5.0	.0	****	3.47	.06	3.62	11.03	27.00			3	12	16	.14		.04			
410.0	415.0	70971	5.0	.0	****	3.35	.16	.66	2.96	12.20			3	12	16	.14		.04			
415.0	420.0	70972	5.0	.0	****	3.57	.08	2.96	7.80	25.70			3	12	16	.11		.04			
420.0	425.0	70973	5.0	.0	****	3.64	.04	5.10	14.30	34.00			4	9	13	.12		.04			
425.0	430.0	70974	5.0	.0	****	2.89	.23	1.98	3.54	19.70			4	9	13	.13		.04			
430.0	435.0	70975	5.0	.0	****	3.48	.12	5.79	9.02	43.20			4	9	13	.12		.04			
435.0	440.0	70976	5.0	.0	****	3.19	.16	3.52	7.93	23.30			4	9	13	.11		.04			
440.0	445.0	70977	5.0	.0	****	3.33	.07	2.36	6.47	32.90			3	10	14	.11		.03			
445.0	450.0	70978	5.0	.0	****	3.40	.06	4.92	12.00	28.20			3	10	14	.10		.03			
450.0	455.0	70979	5.0	.0	****	3.28	.14	3.52	7.38	28.60			3	10	14	.09		.03			
455.0	460.0	70980	5.0	.0	****	3.47	.07	3.86	9.41	39.90			3	10	14	.11		.03			
460.0	465.0	70981	5.0	.0	****	3.45	.11	1.80	5.08	27.20			5	10	15	.23		.03			
465.0	470.0	70982	5.0	.0	****	3.31	.17	1.90	4.15	28.60			5	10	15	.10		.03			

DDH: 66E-01 UTM-N: 7541.5 UTM-E: 15604.0 UTM-ELEV: 4012.0 TOTAL DEPTH: 452.5 SECTION: 132
 RFE: S2 RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
150.0	155.0	70988	5.0	.0	2C3	3.05	.14	.10	.16	5.90				7	13	20	.30				.08
155.0	160.0	70989	5.0	.0	2C3	3.32	.29	.52	.14	16.90				7	13	20	.05				.08
160.0	165.0	70990	5.0	.0	2D0	3.74	.10	3.25	6.53	60.70		.14	7	13	20	.32				.08	
165.0	170.0	70991	5.0	.0	2D0	3.41	.12	3.13	5.91	53.30		.01	6	11	18	1.76				.17	
170.0	175.0	70992	5.0	.0	2D0	2.92	.04	2.94	3.57	47.40		.01	6	11	18	.40				.17	
175.0	180.0	70993	5.0	.0	2B0	3.17	.12	1.68	2.92	32.70		.01	6	11	18	.28				.17	
180.0	185.0	70994	5.0	.0	2F4	4.45	.14	6.06	10.10	49.10		.01	6	11	18	.08				.17	
185.0	190.0	70995	5.0	.0	2F4	4.93	.06	5.00	9.06	41.50		1.58	10	25	36	.02				.11	
190.0	195.0	70996	5.0	.0	2H4	4.31	.27	4.44	8.85	45.30		.14	10	25	36	.06				.11	
195.0	200.0	70997	5.0	.0	2H34	4.28	.19	2.21	5.97	22.00		.06	10	25	36	.12				.11	

DDH: 66E-04 UTM-N: 7352.0 UTM-E: 15416.0 UTM-ELEV: 4023.0 TOTAL DEPTH: 450.0 SECTION: 132
 RFE: S2 RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
130.0	135.0	71003	5.0	.0	2D4	3.28	.18	7.49	5.17	133.80		.06	6	16	23	.77		.20			
135.0	140.0	71004	5.0	.0	2C2	3.06	.11	.36	.12	6.80		.01	6	16	23	.38		.20			
140.0	145.0	71005	5.0	.0	2F4	4.04	.14	7.88	6.40	112.50		.14	6	16	23	1.95		.20			
145.0	150.0	71006	5.0	.0	2D0	3.37	.14	5.49	3.95	69.40		.01	6	16	23	.32		.20			
150.0	155.0	71007	5.0	.0	2F4	5.34	.12	4.23	6.10	31.30		.07	6	16	23	.02		.20			
155.0	160.0	71008	5.0	.0	2F4	4.84	.04	4.87	9.96	48.80		.07	7	26	33	.02		.07			
160.0	165.0	71009	5.0	.0	2F4	4.85	.05	6.30	11.33	74.80		.07	7	26	33	.02		.07			
165.0	170.0	71010	5.0	.0	2F4	4.96	.21	4.41	7.63	54.20		.01	7	26	33	.23		.07			
170.0	175.0	71011	5.0	.0	2D0	3.57	.21	2.96	5.06	42.60		.01	7	26	33	.52		.07			
175.0	180.0	71012	5.0	.0	2D0	3.43	.14	1.95	3.42	30.50		.01	11	10	22	1.04		.06			
180.0	185.0	71013	5.0	.0	2C0	3.37	.23	1.28	2.51	19.90		.01	11	10	22	.44		.06			
185.0	190.0	71014	5.0	.0	2H4	3.87	.25	4.18	8.17	71.40		.07	11	10	22	1.63		.06			
190.0	195.0	71015	5.0	.0	2CH	3.11	.10	2.21	3.62	41.50		.01	11	10	22	.55		.06			
195.0	200.0	71016	5.0	.0	2D1	3.22	.09	1.76	2.88	31.30		.14	3	12	15	.52		.06			
200.0	205.0	71017	5.0	.0	2C1	3.10	.06	.37	.69	9.80			3	12	15	.81		.06			
205.0	210.0	71018	5.0	.0	2C1	3.08	.10	.19	1.64	8.00			3	12	15	.54		.06			
210.0	215.0	71019	5.0	.0	2D1	3.25	.10	1.73	4.08	41.30		.21	3	12	15	.67		.06			
215.0	220.0	71020	5.0	.0	2A54	3.26	.09	3.77	4.67	66.20		.21	4	5	10	.68		.04			
220.0	225.0	71021	5.0	.0	2A51	3.21	.11	.98	1.90	30.50		.27	4	5	10	.68		.04			
225.0	230.0	71022	5.0	.0	2A5	2.61		.83	1.32	16.90			4	5	10	.95		.04			
230.0	235.0	71023	5.0	.0	2A5	2.56		.46	.55	6.30			4	5	10	.86		.04			
235.0	240.0	71024	5.0	.0	2A5	2.69		.50	1.30	8.00			5	3	9	.54		.04			
240.0	245.0	71025	5.0	.0	2A5	2.61	.05	.52	1.59	9.40			5	3	9	.37		.04			
245.0	250.0	71026	5.0	.0	2A5	2.93	.31		.32	14.30			5	3	9	.25		.04			

DDH: 66E-05 UTM-N: 7536.0 UTM-E: 15206.0 UTM-ELEV: 4014.0 TOTAL DEPTH: 346.8 SECTION: 130
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS----						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
240.0	245.0	71033	5.0	.0	****	3.02	.16		.01	5.50			5	18	23	.33		.09			
245.0	250.0	71034	5.0	.0	2C8	3.15	.10	.88	1.91	15.30			5	18	23	.38		.09			
250.0	255.0	71035	5.0	.0	2CA	3.02		.81	1.20	13.60			5	18	23	.94		.09			
255.0	260.0	71036	5.0	.0	2E14	3.38	.24	2.25	4.18	32.20		.07	5	18	23	.35		.09			
260.0	265.0	71037	5.0	.0	2E80	3.59	.61	1.30	1.92	23.20		.01	5	18	23	.05		.09			
265.0	270.0	71038	5.0	.0	2E80	4.72	.20	2.01	1.36	25.30		.01	5	36	41	.06		.15			
270.0	275.0	71039	5.0	.0	2E84	4.76	.07	1.72	3.03	20.70		.01	5	36	41	.03		.15			
275.0	280.0	71040	5.0	.0	2E84	4.67	.05	2.25	3.60	21.20		.01	5	36	41	.02		.15			
280.0	285.0	71041	5.0	.0	2E84	4.78		2.77	5.18	25.30		.07	5	36	41	.02		.15			
285.0	290.0	71042	5.0	.0	2E4	4.10	.39	2.27	4.73	31.50		.07	30	14	44	.14		.05			
290.0	295.0	71043	5.0	.0	2H4	4.08	.73	2.01	3.62	37.60		.07	30	14	44	.07		.05			
295.0	300.0	71044	5.0	.0	2H0	3.90	.57	.97	2.41	34.10		.07	30	14	44	.05		.05			
300.0	305.0	71045	5.0	.0	2H0	3.92	.49	1.43	2.55	47.30		.07	30	14	44	.06		.05			
305.0	310.0	71046	5.0	.0	2C0	2.90	.16	.41	2.35	13.00		.01	7	7	15	.27		.11			
310.0	315.0	71047	5.0	.0	2D0	2.88	.13	1.82	4.48	30.60		.07	7	7	15	.20		.11			
315.0	320.0	71048	5.0	.0	2D4	3.34	.24	7.86	12.25	116.80		.01	7	7	15	.18		.11			
320.0	325.0	71049	5.0	.0	2D0	3.05	.07	2.14	4.27	70.10			7	7	15	.49		.11			
325.0	330.0	71050	5.0	.0	2A0	2.61	.02	.83	1.50	17.50			2	1	3	.88		.03			
330.0	335.0	71051	5.0	.0	2A0	2.69	.03	.87	1.23	18.50			2	1	3	.62		.03			
335.0	340.0	71052	5.0	.0	2A0	2.54	.01	.54	1.54	11.40			2	1	3	.77		.03			
340.0	345.0	71053	5.0	.0	2A0	2.69	.03	.78	1.82	22.20			2	1	3	.35		.03			

DDH: 66E-06 UTM-N: 7736.4 UTM-E: 15399.4 UTM-ELEV: 4008.8 TOTAL DEPTH: 500.0 SECTION: 130
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
205.0	210.0	71057	5.0	.0	2A4	3.52	.09	1.93	3.38	8.00				2	21	24	.03				.04
210.0	215.0	71058	5.0	.0	2C0	3.45	.07	.47	2.86	4.50				2	21	24	.04				.04
215.0	220.0	71059	5.0	.0	2D0	3.59	.03	1.76	5.85	14.60				2	21	24	.11				.04
220.0	225.0	71060	5.0	.0	2D0	3.28	.09	4.07	4.44	56.70				8	9	18	7.01				.40
225.0	230.0	71061	5.0	.0	2D4	3.99	.13	10.35	8.13	137.90				8	9	18	1.64				.40
230.0	235.0	71062	5.0	.0	2D0	2.98	.04	2.44	2.26	31.50				8	9	18	2.45				.40
235.0	240.0	71063	5.0	.0	2E0	3.37	.07	3.76	2.22	52.00				8	9	18	5.59				.40
240.0	245.0	71064	5.0	.0	1D4/9	2.99	.06	1.25	1.22	21.70		.01	8	15	24	4.48				.13	
245.0	250.0	71065	5.0	.0	1D4	2.75	.04	.66	.95	17.60		.06	8	15	24	2.34				.13	
250.0	255.0	71066	5.0	.0	2J3	4.31	.31	2.94	5.90	38.30			8	15	24	.50				.13	
255.0	260.0	71067	5.0	.0	2J3	4.31	.24	2.41	5.05	33.60			8	15	24	.04				.13	
260.0	265.0	71068	5.0	.0	2J3	4.33	.36	2.58	4.35	31.90			6	25	32	.04				.07	
265.0	275.0	71069	10.0	.0	2F0	4.82	.12	2.97	6.01	18.50			6	25	32	.02				.07	
275.0	280.0	71070	5.0	.0	2D0	2.95	.04	2.10	4.03	20.30		.06	6	25	32	.54				.07	
280.0	285.0	71071	5.0	.0	2D0	2.86	.02	2.48	5.33	27.70		.06	5	9	15	.59				.04	
285.0	290.0	71072	5.0	.0	2D0	3.53	.21	3.90	5.04	51.00		.20	5	9	15	.13				.04	
290.0	295.0	71073	5.0	.0	2D0	2.95	.02	1.07	4.46	22.10		.14	5	9	15	.43				.04	
295.0	300.0	71074	5.0	.0	2D0	2.94	.03	1.42	4.64	26.50		.14	5	9	15	.31				.04	
300.0	305.0	71075	5.0	.0	2A4	2.78	.02	1.30	2.77	25.90		.34	3	2	6	.21				.02	
305.0	311.0	71076	6.0	.0	2D0	3.05	.07	1.92	3.72	34.70		.34	3	2	5	.13				.01	

DDH: 66E-07 UTM-N: 7131.0 UTM-E: 15217.0 UTM-ELEV: 4018.0 TOTAL DEPTH: 504.0 SECTION: 132
 RFE: S2 RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
215.0	220.0	71082	5.0	.0	2B0	2.90	.06	.22	.20	10.40				3	3	7	.49		.04		
220.0	225.0	71083	5.0	.0	2D4	3.03	.07	3.62	7.28	60.30		.07	3	3	7	.11		.04			
225.0	230.0	71084	5.0	.0	2C5	2.85	.05	2.65	1.66	37.00		.07	3	3	7	.18		.04			
230.0	231.6	71085	1.6	.0	2A4	2.97	.04	1.86	3.17	30.20		.07	6	5	11	.45		.14			
231.6	236.0	71086	4.4	.0	2C0	2.83	.03	.76	1.48	12.30		.07	6	5	11	.38		.14			
236.0	241.0	71087	5.0	.0	2A4	3.08	.03	1.55	3.35	29.00		.14	6	5	11	.39		.14			
241.0	245.0	71088	4.0	.0	2D4	3.98	.12	5.52	11.38	97.70		.07	6	5	11	.07		.14			
245.0	250.0	71089	5.0	.0	2D4	3.02	.06	10.62	14.65	197.50		.14	6	5	11	.17		.14			

DDH: 66E-09 UTM-N: 7943.0 UTM-E: 15592.0 UTM-ELEV: 4037.0 TOTAL DEPTH: 546.0 SECTION: 130
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
230.0	234.0	71101	4.0	.0	2CE	3.13	.28		.27	6.30			3 17	20	.17		.05				
234.0	240.0	71102	6.0	.0	2D4	3.97	.03	5.73	11.14	33.60		1.37	3 17	20	.11		.05				
285.0	290.0	71104	5.0	.0	2E0	3.08	.25	.87	.21	23.10			10 25	36	.30		.18				
290.0	295.0	71105	5.0	.0	2E0	4.04	.25	.01		5.00			10 25	36	.03		.18				
295.0	300.0	71106	5.0	.0	2E0	3.46	1.03	.87	.65	39.00			10 25	36	.05		.18				
300.0	310.0	71107	10.0	.0	1D/2E	3.76	.42	3.97	2.11	87.00		1.78	10 25	36	3.09		.18				
310.0	315.0	71108	5.0	.0	2E4	3.57	.20	2.39	1.95	35.80		.34	7 32	40	.05		.33				
315.0	320.0	71109	5.0	.0	2E84	4.63	.24	2.48	2.37	27.30		.82	7 32	40	.03		.33				
320.0	325.0	71110	5.0	.0	2E84	4.95	.27	3.46	2.22	38.30		.41	7 32	40	.02		.33				
325.0	330.0	71111	5.0	.0	2E1	3.41	.27	1.15	.69	13.40		.27	7 32	40	.08		.33				
330.0	335.0	71112	5.0	.0	2B0	4.80	.23	.45		8.10		.14	2 39	41	.06		.06				
335.0	340.0	71113	5.0	.0	2E4	4.81	.19	2.52	2.65	22.90		.07	2 39	41	.04		.06				
340.0	345.0	71114	5.0	.0	2E0	4.76	.26	1.18	.78	22.80		.07	2 39	41	.04		.06				
345.0	350.0	71115	5.0	.0	2E4	4.83	.15	3.08	4.28	28.70		.07	2 39	41	.03		.06				
350.0	355.0	71116	5.0	.0	2E4	4.32	.18	2.95	5.39	29.10		.07	1 32	34	.03		.06				
355.0	360.0	71117	5.0	.0	2CE	3.80	.08	1.91	.39	27.40			1 32	34	.02		.06				
360.0	365.0	71118	5.0	.0	2E0	4.39	.10	1.08	.71	12.50			1 32	34	.02		.06				
365.0	370.0	71119	5.0	.0	2E0	3.91	.14	.52	.50	11.20			1 32	34	.02		.06				
370.0	375.0	71120	5.0	.0	2C0	3.17	.08	.78	2.42	9.90		.21	1 26	27	.15		.02				
375.0	380.0	71121	5.0	.0	2F4	4.09	.05	5.41	8.10	38.10		.14	1 26	27	.08		.02				
380.0	385.0	71122	5.0	.0	2CE	3.91	.21	1.54	2.11	17.60		.07	1 26	27	.08		.02				
385.0	390.0	71123	5.0	.0	2CE4	4.23	.20	2.08	3.17	19.00		.07	1 26	27	.11		.02				
390.0	395.0	71124	5.0	.0	2CE	4.01	.42	.62	1.00	9.00		.07	5 28	34	.02		.21				
395.0	400.0	71125	5.0	.0	2C0	4.20	.43	.39	1.00	9.10		1.10	5 28	34	.04		.21				
400.0	405.0	71126	5.0	.0	2D0	4.36	.36	1.87	2.32	13.60		.07	5 28	34	.01		.21				
405.0	410.0	71127	5.0	.0	2D0	3.86	.25	3.04	3.46	17.90			5 28	34	.03		.21				
410.0	415.0	71128	5.0	.0	2E8	4.12	.27	1.13	1.81	9.30		.01	4 25	30	.03		.19				
415.0	420.0	71129	5.0	.0	2CE4	3.71	.19	2.20	4.07	13.10			4 25	30	.04		.19				
420.0	425.0	71130	5.0	.0	2CE4	3.43	.08	.57	5.07	6.60			4 25	30	.15		.19				
425.0	430.0	71131	5.0	.0	2CE	4.15	.30	.41	1.73	7.50			4 25	30	.04		.19				
430.0	435.0	71132	5.0	.0	2CE4	3.79	.14	1.34	3.48	8.00		.03	3 24	27	.03		.07				
435.0	440.0	71133	5.0	.0	2EC4	3.81	.06	3.49	8.02	18.50		.03	3 24	27	.11		.07				
440.0	446.5	71134	6.5	.0	2EC4	4.16	.09	4.17	10.35	15.80		.03	3 24	27	.04		.07				

DDH: 67-02 UTM-N: 8171.5 UTM-E: 15753.1 UTM-ELEV: 4123.0 TOTAL DEPTH: 606.0 SECTION: 130
RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS----				-----ASSAYS-----																
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
438.5	444.0	71146	5.5	.0	2DE	2.79	.09	1.79	2.94	13.10		.07	4	19	23	.04		.05		
444.0	448.5	71147	4.5	.0	2DE	3.30	.11	3.37	10.02	20.20		.14	4	19	23	.09		.05		

DDH: 67-03 UTM-N: 8177.1 UTM-E: 14934.9 UTM-ELEV: 4039.0 TOTAL DEPTH: 999.0 SECTION: 126
 RFE: S2 RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
439.0	444.0	71156	5.0	.0	2C0	2.93	.07	1.64	.11	32.90			5	7	12	.68		.16			
444.0	449.0	71157	5.0	.0	2D4	3.41	.10	4.33	6.28	48.90			.27	5	7	12	.24		.16		
449.0	454.0	71158	5.0	.0	2B4	3.90	.20	3.25	8.38	41.40			.62	4	19	24	.23		.17		
454.0	459.0	71159	5.0	.0	2EG	4.65	.04	4.94	6.66	66.60		2.54	4	19	24	16.04		.17			
459.0	464.0	71160	5.0	.0	2G4	4.62	.14	8.08	7.00	115.40			.01	4	19	24	21.96		.17		
464.0	469.0	71161	5.0	.0	2G/1D	3.83	.03	2.83	4.68	46.00			.07	4	19	24	26.51		.17		
509.0	514.0	71164	5.0	.0	2B0	3.14	.05	2.09	2.26	31.20			.07	14	13	28	7.05		.21		
514.0	519.0	71165	5.0	.0	2B4	4.03	.16	5.00	6.45	79.40			.07	14	13	28	2.97		.21		
519.0	524.0	71166	5.0	.0	2D4	3.97	.20	4.50	7.05	67.40			.01	14	13	28	.64		.21		
524.0	529.0	71167	5.0	.0	2H4	4.34	.25	6.18	9.90	68.50			.01	14	13	28	.07		.21		
529.0	534.0	71168	5.0	.0	2E4	4.34	.25	5.20	9.88	53.20			.07	17	23	40	.03		.22		
534.0	539.0	71169	5.0	.0	2H8	4.53	.12	2.29	1.52	36.20			.01	17	23	40	.04		.22		
539.0	544.0	71170	5.0	.0	2H8	4.36	.27	1.07	1.02	16.30			.01	17	23	40	.04		.22		
544.0	549.0	71171	5.0	.0	2E0	4.59	.13	1.66	1.61	16.60			.01	17	23	40	.03		.22		
549.0	554.0	71172	5.0	.0	2E4	4.55	.07	5.49	9.65	52.30			.07	8	22	31	.02		.09		
554.0	559.0	71173	5.0	.0	2EH	4.74	.21	5.70	9.84	38.20			.07	8	22	31	.02		.09		
559.0	564.0	71174	5.0	.0	2HF	4.90	.12	5.06	9.59	34.70			.07	8	22	31	.03		.09		
564.0	569.0	71175	5.0	.0	2C0	3.34	.13	.72	1.36	9.80			.07	8	22	31	.25		.09		
569.0	574.0	71176	5.0	.0	2C0	3.61	.05	1.09	1.02	60.70			.62	3	23	27	.25		.14		
574.0	579.0	71177	5.0	.0	2D0	3.54	.03	1.11	3.79	17.20			.27	3	23	27	.27		.14		
579.0	584.0	71178	5.0	.0	2F4	4.18	.24	5.45	10.90	40.60			.01	3	23	27	.04		.14		
584.0	589.0	71179	5.0	.0	2F0	4.12	.13	2.33	7.56	33.40			.07	3	23	27	.04		.14		
589.0	594.0	71180	5.0	.0	2D0	3.46	.21	2.32	4.46	25.40			.07	11	11	22	.28		.08		
594.0	599.0	71181	5.0	.0	2ED	3.07	.14	3.18	6.11	25.00			.14	11	11	22	.31		.08		
599.0	604.0	71182	5.0	.0	2H4	3.69	.10	1.71	6.31	38.90			.07	11	11	22	.06		.08		
604.0	609.0	71183	5.0	.0	2A4	3.54	.06	1.19	4.63	28.10			.07	11	11	22	.27		.08		
609.0	614.0	71184	5.0	.0	2A4	3.05	.08	1.24	2.88	18.80			.07	4	5	10	.16		.03		
614.0	619.0	71185	5.0	.0	2A4	2.84	.04	1.45	4.95	22.70			.01	4	5	10	.21		.03		
619.0	624.0	71186	5.0	.0	2A0	2.77	.08	.72	2.78	21.80			.07	4	5	10	.20		.03		
624.0	629.0	71187	5.0	.0	2A0	2.92	.09	1.10	1.75	18.10				4	5	10	.17		.03		

DDH: 67-04 UTM-N: 8162.6 UTM-E: 15361.3 UTM-ELEV: 4081.0 TOTAL DEPTH: 742.0 SECTION: 128
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
419.0	424.0	71197	5.0	.0	2CF	3.90	.20	.16	4.35	26.60		.21	3	29	32	.23		.04			
424.0	429.0	71198	5.0	.0	2CE4	4.37	.04	2.64	4.85	5.50		.14	3	29	32	.08		.04			
429.0	434.0	71199	5.0	.0	2F1	4.03	.07	.37	6.40	24.80		.27	3	29	32	.14		.04			
434.0	439.0	71200	5.0	.0	1D4	2.77	.12	1.51	1.23	7.30		.14	3	7	11	.50		.12			
439.0	444.0	71201	5.0	.0	1D4	3.15	.07	1.56	2.98	27.30		.48	3	7	11	6.88		.12			
444.0	449.0	71202	5.0	.0	1D4	2.75	.03	.56	.18	4.00			3	7	11	2.27		.12			
449.0	454.0	71203	5.0	.0	1D4	2.72	.04	.78	.95	9.80			3	7	11	9.88		.12			
454.0	459.0	71204	5.0	.0	2DE	3.10	.06	2.68	2.34	14.90		.07	4	18	22	5.03		.12			
459.0	464.0	71205	5.0	.0	2EG	4.49	.02	1.93	5.39	37.00		.21	4	18	22	11.22		.12			
464.0	469.0	71206	5.0	.0	2DE	3.90	.05	1.77	4.40	31.30		.27	4	18	22	.71		.12			
469.0	474.0	71207	5.0	.0	1D4	3.03	.14	.79	.50	15.30		.07	4	18	22	1.54		.12			
474.0	479.0	71208	5.0	.0	1D4	2.94	.07	.74	1.06	14.10		.01	7	24	31	.90		.18			
479.0	484.0	71209	5.0	.0	2E3	3.54	.35	1.56	1.77	32.50			7	24	31	.24		.18			
484.0	489.0	71210	5.0	.0	2E1	4.43	.21	1.07	1.45	18.20		.62	7	24	31	.21		.18			
489.0	494.0	71211	5.0	.0	2CE	4.65	.23	2.14	1.77	23.50		.21	7	24	31	.13		.18			
494.0	499.0	71212	5.0	.0	2E4	5.29	.23	4.34	3.85	37.50		.21	3	39	42	.03		.10			
499.0	504.0	71213	5.0	.0	2E0	4.81	.13	2.23	1.71	20.30		.07	3	39	42	.05		.10			
504.0	509.0	71214	5.0	.0	2E4	5.02	.22	3.00	2.19	24.90		.01	3	39	42	.03		.10			
509.0	514.0	71215	5.0	.0	2E0	4.97	.14	2.09	1.58	24.90		.27	3	39	42	.03		.10			
514.0	519.0	71216	5.0	.0	2E0	5.02	.22	1.23	.85	20.60		.27	4	37	41	.02		.13			
519.0	524.0	71217	5.0	.0	2E4	4.62	.18	2.25	1.90	28.30		.21	4	37	41	.02		.13			
524.0	529.0	71218	5.0	.0	2E04	4.74	.20	2.62	3.16	35.80		.14	4	37	41	.02		.13			
529.0	534.0	71219	5.0	.0	2F0	4.76	.18	2.94	4.55	31.70		.07	4	37	41	.02		.13			
534.0	539.0	71220	5.0	.0	2E4	5.44	.14	6.57	4.33	50.60			2	31	33	.02		.03			
539.0	544.0	71221	5.0	.0	2CE	3.91	.03	1.36	.81	11.10		.27	2	31	33	.02		.03			
544.0	549.0	71222	5.0	.0	2E4	4.16	.10	3.62	5.13	26.30		.21	2	31	33	.03		.03			
549.0	554.0	71223	5.0	.0	2E4	4.36	.19	1.96	3.36	14.30			2	31	33	.03		.03			
554.0	559.0	71224	5.0	.0	2E0	4.01	.45	1.44	1.97	19.20		.14	6	27	33	.02		.27			
559.0	564.0	71225	5.0	.0	2F14	5.20	.25	6.28	10.60	40.10		.07	6	27	33	.02		.27			
564.0	569.0	71226	5.0	.0	2E4	5.05	.22	5.48	7.75	31.60		.01	6	27	33	.02		.27			
569.0	574.0	71227	5.0	.0	2CE	4.18	.35	.55	1.39	9.00		.07	6	27	33	.02		.27			
574.0	579.0	71228	5.0	.0	2CE	3.82	.28	1.86	1.90	18.40		.14	5	26	32	.04		.21			
579.0	584.0	71229	5.0	.0	2CE	3.65	.18	.46	1.55	7.80		.07	5	26	32	.06		.21			
584.0	589.0	71230	5.0	.0	2EC	3.95	.28	.15	1.53	5.20		.01	5	26	32	.13		.21			
589.0	594.0	71231	5.0	.0	2F1	4.43	.15	2.51	4.88	8.10		.01	5	26	32	.03		.21			
594.0	599.0	71232	5.0	.0	2D4	3.90	.14	4.24	8.17	17.60			8	16	24	.07		.06			
599.0	604.0	71233	5.0	.0	2D0	3.55	.12	.75	2.56	6.00			8	16	24	.10		.06			
604.0	609.0	71234	5.0	.0	2D4	3.99	.13	4.10	9.52	23.60			8	16	24	.10		.06			
609.0	614.0	71235	5.0	.0	2F4	4.09	.04	5.38	12.00	16.00			8	16	24	.09		.06			
614.0	619.0	71236	5.0	.0	2F4	4.09	.05	7.04	14.50	18.20			3	20	24	.09		.02			
619.0	624.0	71237	5.0	.0	2F4	4.15	.06	6.34	12.40	18.80			3	20	24	.10		.02			
624.0	629.0	71238	5.0	.0	2F4	4.21	.06	5.77	14.20	20.00			3	20	24	.10		.02			
629.0	634.0	71239	5.0	.0	2F4	4.55	.07	6.78	16.50	27.00			3	20	24	.04		.02			
634.0	639.0	71240	5.0	.0	2F4	4.35	.03	7.61	10.70	42.20			12	14	26	.03		.05			
639.0	644.0	71241	5.0	.0	2E4	4.43	.64	3.14	5.97	24.30			12	14	26	.03		.05			
644.0	649.0	71242	5.0	.0	2H4	3.20	.08	2.29	1.85	28.80			12	14	26	.19		.05			

DDH: 67-05 UTM-N: 7942.0 UTM-E: 15176.7 UTM-ELEV: 4028.0 TOTAL DEPTH: 569.0 SECTION: 128
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
308.0	313.0	71249	5.0	.0	2DE	3.44	.09	3.58	4.67	56.10		.07	12	12	25	1.60		.09			
313.0	318.0	71250	5.0	.0	2DE4	4.07	.21	3.66	7.95	57.60		.07	12	12	25	.62		.09			
360.0	365.0	71252	5.0	.0	2D6	3.29	.09	1.84	2.63	31.50		.01	30	7	38	10.66		.06			
365.0	370.0	71253	5.0	.0	2H4	4.51	.21	7.13	11.30	74.30			30	7	38	.15		.06			
370.0	375.0	71254	5.0	.0	2H4	4.59	.18	7.00	14.00	68.10		.07	30	7	38	.02		.06			
375.0	380.0	71255	5.0	.0	2H4	4.22	.22	2.20	5.86	30.60		.07	30	7	38	.05		.06			
380.0	385.0	71256	5.0	.0	2C0	3.42	.16	.61	.76	17.10			22	8	31	.02		.05			
385.0	390.0	71257	5.0	.0	2C0	3.35	.14	.55	.62	10.50			22	8	31	.07		.05			
390.0	395.0	71258	5.0	.0	2DH	3.81	.19	1.82	3.93	24.50		.07	22	8	31	.11		.05			
395.0	400.0	71259	5.0	.0	2D7	3.63	.45	1.40	3.27	21.00		.41	22	8	31	.23		.05			
400.0	405.0	71260	5.0	.0	2H4	4.11	.28	1.86	3.86	23.40		.27	30	12	43	.09		.17			
405.0	410.0	71261	5.0	.0	2H4	4.10	.26	1.53	3.52	30.00		.01	30	12	43	.02		.17			
410.0	415.0	71262	5.0	.0	2HF4	4.39	.26	4.59	10.20	40.90		.01	30	12	43	.15		.17			
415.0	420.0	71263	5.0	.0	2F4	4.42	.13	4.50	8.15	41.50		.07	30	12	43	.03		.17			
420.0	425.0	71264	5.0	.0	2F4	4.29	.16	5.21	9.17	38.50			5	30	35	.03		.17			
425.0	430.0	71265	5.0	.0	2FE	4.44	.16	3.68	5.58	26.10		.07	5	30	35	.05		.17			
430.0	435.0	71266	5.0	.0	2E84	3.90	.11	.94	2.13	8.40		.01	5	30	35	.03		.17			
435.0	440.0	71267	5.0	.0	2F0	3.27	.08	1.89	4.93	8.60		.07	5	30	35	.05		.17			
440.0	445.0	71268	5.0	.0	2H4	2.85	.24	2.46	5.74	10.80		.01	13	10	23	.04		.06			
445.0	450.0	71269	5.0	.0	2D0	3.79	.27	2.96	5.76	22.40		.07	13	10	23	.11		.06			
450.0	455.0	71270	5.0	.0	2A4	3.15	.07	2.68	7.89	36.40		.14	13	10	23	.26		.06			
455.0	460.0	71271	5.0	.0	2D0	3.02	.06	1.59	4.54	26.20		.01	13	10	23	.39		.06			
460.0	465.0	71272	5.0	.0	2C0	3.09	.21	1.04	2.18	16.30			8	11	20	.34		.06			
465.0	470.0	71273	5.0	.0	2EA	3.36	.14	2.35	4.82	32.50		.07	8	11	20	.22		.06			
470.0	475.0	71274	5.0	.0	2DE	3.50	.23	2.77	4.80	44.10		.07	8	11	20	.13		.06			
475.0	480.0	71275	5.0	.0	2DE	3.33	.12	1.47	3.04	28.50		.14	8	11	20	.13		.06			
480.0	485.0	71276	5.0	.0	2A4	3.02	.09	1.38	3.95	29.60		.14	4	3	7	.18		.04			
485.0	490.0	71277	5.0	.0	2A0	2.75	.08	.98	1.30	23.70			4	3	7	.24		.04			

DDH: 67-06 UTM-N: 8566.2 UTM-E: 15016.0 UTM-ELEV: 4135.0 TOTAL DEPTH: 852.5 SECTION: 124
 RFE: S2 RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
485.0	490.0	71285	5.0	.0	2A0	3.12	.17	.13	.30	6.30				3 16	19	.22					.08
490.0	495.0	71286	5.0	.0	2EA	4.20	.21	.03	.14	4.60				3 16	19	.02					.08
495.0	500.0	71287	5.0	.0	2A0	3.10	.16	.11	1.34	7.50				3 16	19	.09					.08
500.0	505.0	71288	5.0	.0	2A0	2.79	.14	.07	.25	4.70				3 16	19	.14					.08
505.0	510.0	71289	5.0	.0	2A0	2.96	.11	.12	.91	5.80				3 12	15	.38					.09
510.0	515.0	71290	5.0	.0	2C0	3.57	.14	.88	1.16	10.90				3 12	15	.11					.09
515.0	520.0	71291	5.0	.0	2C0	3.10	.02	.08	.69	1.70				3 12	15	.37					.09
588.0	593.0	71293	5.0	.0	2F0	4.33	.11	4.70	7.80	60.50				6 15	21	6.36					.10
593.0	598.0	71294	5.0	.0	1D/2E	3.33	.18	2.58	2.61	39.40				6 15	21	4.93					.10
598.0	603.0	71295	5.0	.0	1D4	3.59	.11	2.48	3.09	50.90				6 15	21	8.09					.10
603.0	608.0	71296	5.0	.0	2GE	3.95	.18	2.98	4.12	55.00				6 15	21	16.56					.10
608.0	613.0	71297	5.0	.0	2D0	4.25	.17	4.40	3.45	84.10				3 29	33	3.15					.12
613.0	618.0	71298	5.0	.0	2C0	4.36	.18	2.13	.83	55.70				3 29	33	.13					.12
618.0	623.0	71299	5.0	.0	2D0	3.89	.11	4.10	4.62	52.90				3 29	33	.06					.12
623.0	628.0	71300	5.0	.0	2D0	5.59	.10	2.74	3.57	33.80				3 29	33	5.28					.12
628.0	633.0	71301	5.0	.0	2CG	4.71	.01	2.94	4.15	36.10				28 28	2.31						.01
633.0	638.0	71302	5.0	.0	2C0	4.37	.01	.60	1.14	7.90				28 28	1.69						.01
638.0	643.0	71303	5.0	.0	2C0	3.76	.01	.09	.11	2.60				28 28	.06						.01
643.0	648.0	71304	5.0	.0	2C0	3.12	.01	.05	.10	3.30				28 28	.03						.01
648.0	653.0	71305	5.0	.0	2C0	3.53		.06	.10	3.30				28 28	.02						.03
653.0	658.0	71306	5.0	.0	2C0	3.48	.01	.06	.10	3.00				28 28	.02						
658.0	663.0	71307	5.0	.0	2C0	3.99	.16	.05	.10	3.10				28 28	.03						
663.0	668.0	71308	5.0	.0	2GE	4.65	.08	1.70	2.38	16.70		.07		28 28	.07						.03
668.0	673.0	71309	5.0	.0	2G4	4.73	.08	3.71	6.63	29.20		.01	3 27	31 19.61							.17
673.0	678.0	71310	5.0	.0	2F64	4.61	.07	4.80	8.06	38.40		.14	3 27	31 4.55							.17
678.0	683.0	71311	5.0	.0	2GE4	4.89	.08	4.95	7.78	48.80		.07	3 27	31 12.57							.17
683.0	688.0	71312	5.0	.0	2E4	4.68	.24	3.73	4.70	44.00		.21	3 27	31 .17							.17
688.0	693.0	71313	5.0	.0	2E4	4.73	.16	2.65	1.97	25.80		.07	1 33	35 .04							.05
693.0	698.0	71314	5.0	.0	2E4	5.10	.10	4.45	2.93	42.30		.07	1 33	35 .02							.05
698.0	703.0	71315	5.0	.0	2E0	4.74	.17	2.39	1.29	23.60		.21	1 33	35 .04							.05
703.0	708.0	71316	5.0	.0	2C0	4.48	.01	.30	.12	7.90		.07	1 33	35 .02							.05
708.0	713.0	71317	5.0	.0	2C0	4.30	.01	.34	.32	6.30		.07	1 31	33 .02							.08
713.0	718.0	71318	5.0	.0	2G0	4.68	.03	3.64	5.41	38.70		.01	1 31	33 14.99							.08
718.0	723.0	71319	5.0	.0	2EF	4.83	.12	2.58	2.98	34.20		.07	1 31	33 1.48							.08
723.0	728.0	71320	5.0	.0	2EF	4.85	.20	2.70	2.75	43.30		.14	1 31	33 .05							.08
728.0	733.0	71321	5.0	.0	2EF	4.51	.08	4.54	6.26	35.60		.07	4 30	34 .04							.14
733.0	738.0	71322	5.0	.0	2E0	4.38	.21	2.15	2.75	15.20		.01	4 30	34 .03							.14
738.0	743.0	71323	5.0	.0	2EC	3.67	.28	1.27	2.66	13.30		.07	4 30	34 .03							.14
743.0	748.0	71324	5.0	.0	2C0	4.80	.22	.83	2.43	9.70		.75	4 30	34 .02							.14
748.0	753.0	71325	5.0	.0	2F0	4.77	.16	4.36	10.80	19.00		.41	5 21	26 .02							.12
753.0	758.0	71326	5.0	.0	2D0	4.39	.21	2.54	7.03	14.60		.21	5 21	26 .02							.12
758.0	763.0	71327	5.0	.0	2D4	4.28	.12	3.80	9.81	25.30		.14	5 21	26 .02							.12
763.0	768.0	71328	5.0	.0	2A0	2.74	.09	1.13	2.31	15.20		.07	5 21	26 .26							.12
768.0	773.0	71329	5.0	.0	2A0	2.81	.06	1.14	2.12	17.70		.07	6 3	9 .32							.10
773.0	778.0	71330	5.0	.0	2A4	2.75	.06	1.29	3.69	21.00		.21	6 3	9 .24							.10
778.0	783.0	71331	5.0	.0	2A4	3.18	.28	5.67	5.36	74.00		.41	6 3	9 .19							.10

DDH: 67-07 UTM-N: 7743.1 UTM-E: 15007.0 UTM-ELEV: 4005.0 TOTAL DEPTH: 551.0 SECTION: 128
RFE: S2 RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----				-----ASSAYS-----																
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
366.0	371.0	71338	5.0	.0	2DA	3.13	.16	1.58	3.25	29.00		.07	6	4	10	.25		.08		
371.0	376.0	71339	5.0	.0	2DA	2.94	.13	2.86	3.56	53.40		.07	6	4	10	.32		.08		
376.0	381.0	71340	5.0	.0	2DA	2.78	.05	3.36	1.29	73.20		.07	6	4	10	.30		.08		

DDH: 67-08 UTM-N: 8342.2 UTM-E: 15602.2 UTM-ELEV: 4164.0 TOTAL DEPTH: 806.0 SECTION: 128
 RFE: S2 RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
630.0	635.0	71351	5.0	.0	2C7	3.54	.31	.07	.43	9.90			8	9	18	.09		.02			
635.0	640.0	71352	5.0	.0	2C7	3.81	.37	.55	1.15	14.20			3	23	26	.08		.04			
640.0	645.0	71353	5.0	.0	2CE	3.72	.21	.54	2.50	6.60			3	23	26	.06		.04			
645.0	650.0	71354	5.0	.0	2CE	3.87	.14	.80	1.22	5.60			3	23	26	.02		.04			
650.0	655.0	71355	5.0	.0	2D3	4.23	.01	1.99	3.04	6.60		.07	3	23	26	.16		.04			
655.0	660.0	71356	5.0	.0	2C3	3.75	.16	.48	1.52	5.10		.07	4	17	22	.05		.03			
660.0	665.0	71357	5.0	.0	2D3	3.67	.11	2.01	4.93	13.20		.07	4	17	22	.19		.03			
665.0	670.0	71358	5.0	.0	2D43	3.62	.04	4.29	12.25	17.20		.07	4	17	22	.11		.03			
670.0	675.0	71359	5.0	.0	2D43	3.65	.11	5.20	15.50	26.70		.07	4	17	22	.11		.03			
675.0	680.0	71360	5.0	.0	2D0	3.08	.13	1.47	2.59	20.20		.14	4	3	8	.24		.05			
680.0	685.0	71361	5.0	.0	2B4	3.05	.06	8.74	5.11	109.20		.96	4	3	8	.20		.05			
685.0	690.0	71362	5.0	.0	2B4	2.89	.07	2.37	3.27	48.70		.14	4	3	8	.15		.05			
690.0	695.0	71363	5.0	.0	2B/1D	2.94	.02	1.38	4.78	32.50		.07	4	3	8	.13		.05			

DDH: 67-09 UTM-N: 8740.0 UTM-E: 15199.0 UTM-ELEV: 4186.0 TOTAL DEPTH: 800.0 SECTION: 124
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
655.0	660.0	71374	5.0	.0	2C0	3.33	.07	1.23	2.25	10.40		.01	3	22	26	.24		.13			
660.0	665.0	71375	5.0	.0	2CE	4.02	.27	.04	.88	12.30			3	22	26	.05		.13			
665.0	670.0	71376	5.0	.0	2CE	3.87	.47	.05	.50	9.20			3	22	26	.02		.13			
670.0	675.0	71377	5.0	.0	2CE	4.16	.47	.20	1.81	9.70			3	22	26	.01		.13			
675.0	680.0	71378	5.0	.0	2CE	4.18	.20	1.83	1.91	6.80		.01	7	26	33	.01		.15			
680.0	685.0	71379	5.0	.0	2E0	4.35	.25	.60	1.49	8.30			7	26	33	.02		.15			
685.0	690.0	71380	5.0	.0	2E0	4.20	.22	.83	2.49	6.30		.01	7	26	33	.02		.15			
690.0	695.0	71381	5.0	.0	2D7	3.91	.25	1.30	3.84	16.10		.01	7	26	33	.03		.15			
695.0	700.0	71382	5.0	.0	2B4	3.29	.08	4.23	9.38	38.50		.14	3	4	8	.21		.06			
700.0	705.0	71383	5.0	.0	2B4	2.86	.07	1.90	4.01	31.70			3	4	8	.44		.06			
705.0	710.0	71384	5.0	.0	2B4	2.88	.10	1.40	3.40	30.20			3	4	8	.59		.06			
710.0	715.0	71385	5.0	.0	2B4	2.83	.09	1.55	3.09	30.60			3	4	8	.68		.06			
715.0	720.0	71386	5.0	.0	2B4	2.89	.14	1.60	2.83	31.40		.01	3	3	6	.36		.07			
720.0	725.0	71387	5.0	.0	2B0	2.84	.09	.66	1.34	18.60			3	3	6	.23		.07			

DDH: 67-10 UTM-N: 8340.0 UTM-E: 15203.0 UTM-ELEV: 4103.0 TOTAL DEPTH: 741.0 SECTION: 126
 RFE: S2 RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
404.0	409.0	71394	5.0	.0	2C5	3.24	.17	.18	.65	6.10			5	14	19	.13		.04			
409.0	414.0	71395	5.0	.0	2C5	3.45	.10	.20	.61	6.90			5	14	19	.06		.04			
414.0	419.0	71396	5.0	.0	2C5	3.25	.14	.25	.44	7.10			3	16	19	.09		.05			
419.0	424.0	71397	5.0	.0	2C5	3.43	.07	.23	1.02	5.10			3	16	19	.05		.05			
424.0	429.0	71398	5.0	.0	2C0	3.35	.08	.14	1.31	5.90			3	16	19	.05		.05			
429.0	434.0	71399	5.0	.0	2C5	3.12	.17	.10	.81	5.90			3	16	19	.14		.05			
434.0	439.0	71400	5.0	.0	2C5	3.07	.24	3.06	.33	102.80		14.90	3	4	7	.25		.07			
479.0	484.0	71402	5.0	.0	2C0	3.24	.12	2.09	.80	33.90		.14	8	12	21	1.28		.10			
484.0	489.0	71403	5.0	.0	2C0	3.42	.14	2.42	1.66	44.50			8	12	21	2.35		.10			
489.0	494.0	71404	5.0	.0	2H4	3.52	.25	6.77	3.98	133.50			5	26	31	2.48		.11			
494.0	499.0	71405	5.0	.0	1D4/9	4.06	.23	1.51	1.06	28.90		.27	5	26	31	.20		.11			
499.0	506.5	71406	7.5	.0	2E0	4.26	.11	.98	.96	12.30			5	26	31	.09		.11			
506.5	514.0	71407	7.5	.0	2CE	4.29	.04	.78	.36	9.50			5	26	31	.07		.11			
514.0	519.0	71408	5.0	.0	2CE	4.52	.15	.50	.50	9.00			2	30	32	.02		.02			
519.0	524.0	71409	5.0	.0	2C0	4.24	.02	.24	.14	5.90			2	30	32	.02		.02			
524.0	529.0	71410	5.0	.0	2C0	3.29	.08	.67	.04	31.00			2	30	32	.03		.02			
529.0	534.0	71411	5.0	.0	2C0	3.71	.02	1.17	.32	23.90			2	30	32	.04		.02			
534.0	539.0	71412	5.0	.0	2CF	4.05	.35	2.86	4.30	37.20		.14	5	33	39	.02		.15			
539.0	544.0	71413	5.0	.0	2CE	4.28	.09	1.04	.96	13.50		.41	5	33	39	.03		.15			
544.0	549.0	71414	5.0	.0	2E4	4.37	.20	1.76	2.69	24.80		.01	5	33	39	.03		.15			
549.0	554.0	71415	5.0	.0	2E4	4.50	.26	2.79	3.64	31.30		.01	5	33	39	.02		.15			
554.0	559.0	71416	5.0	.0	2E0	4.42	.08	1.30	1.24	18.10		.07	1	36	38	.02		.04			
559.0	564.0	71417	5.0	.0	2E4	4.80	.11	4.63	3.60	41.40		.01	1	36	38	.02		.04			
564.0	569.0	71418	5.0	.0	1D4	4.53	.08	1.10	1.75	18.30		.21	1	36	38	.05		.04			
569.0	574.0	71419	5.0	.0	2D0	4.28	.17	2.63	2.60	23.00		.01	1	36	38	.07		.04			
574.0	579.0	71420	5.0	.0	2C0	4.18	.39	.60	1.11	9.70		.07	5	30	35	.02		.21			
579.0	584.0	71421	5.0	.0	2CF	4.10	.11	3.26	6.70	25.00		.14	5	30	35	.09		.21			
584.0	589.0	71422	5.0	.0	2E84	4.66	.41	1.50	2.66	18.30		.07	5	30	35	.02		.21			
589.0	594.0	71423	5.0	.0	2E84	4.07	.25	1.32	2.88	11.00		.01	5	30	35	.02		.21			
594.0	599.0	71424	5.0	.0	2E84	4.33	.28	2.33	3.85	13.40		.01	4	30	34	.03		.14			
599.0	604.0	71425	5.0	.0	2C0	3.85	.15	.18	.58	5.30		.14	4	30	34	.07		.14			
604.0	609.0	71426	5.0	.0	2D0	4.29	.25	1.60	4.61	9.20		.01	4	30	34	.04		.14			
609.0	614.0	71427	5.0	.0	2F4	4.83	.03	6.07	10.94	27.20		.07	4	30	34	.02		.14			
614.0	619.0	71428	5.0	.0	2F4	4.21	.10	3.95	8.04	19.40		.07	4	18	23	.10		.05			
619.0	624.0	71429	5.0	.0	2D54	3.95	.04	1.40	4.76	10.00		.07	4	18	23	.08		.05			
624.0	629.0	71430	5.0	.0	2D4	3.80	.07	4.55	12.71	26.00		.06	4	18	23	.11		.05			
629.0	634.0	71431	5.0	.0	2D4	3.34	.11	5.18	11.33	52.50		.12	4	18	23	.12		.05			
634.0	639.0	71432	5.0	.0	1D4	2.99	.18	1.29	2.48	33.20		.12	4	18	23	.13		.05			

DDH: 67-11 UTM-N: 8343.0 UTM-E: 14808.0 UTM-ELEV: 4057.0 TOTAL DEPTH: 723.0 SECTION: 124
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
487.0	492.0	71440	5.0	.0	2C0	3.56	.16	3.29	.28	58.00			12	12	25	.50		.26			
492.0	497.0	71441	5.0	.0	2D0	3.98	.18	3.75	6.01	53.30			12	12	25	.68		.26			
497.0	502.0	71442	5.0	.0	2BE4	3.42	.08	5.53	4.24	122.60			12	12	25	2.25		.26			
502.0	507.0	71443	5.0	.0	2E0	3.41	.17	1.78	1.38	25.10			12	12	25	.84		.26			
520.0	525.0	71445	5.0	.0	2EF	3.58	.11	4.99	4.00	90.90		.06	10	18	28	.06		.10			
525.0	530.0	71446	5.0	.0	2EF	4.13	.23	4.55	7.26	70.80		.07	10	18	28	.04		.10			
530.0	535.0	71447	5.0	.0	2E4	3.82	.11	6.97	13.29	113.20		.01	10	18	28	.06		.10			
535.0	540.0	71448	5.0	.0	2B64	3.28	.11	2.13	1.92	46.30		.03	10	18	28	11.19		.10			
540.0	545.0	71449	5.0	.0	2BE4	3.50	.06	3.23	5.70	48.80		.07	10	18	28	.03		.10			
545.0	550.0	71450	5.0	.0	2EF	4.67	.07	3.75	6.54	27.40		.03	10	18	28	.59		.10			
550.0	555.0	71451	5.0	.0	2E24	4.63	.17	3.95	6.28	32.20		.14	4	36	41	.03		.06			
555.0	560.0	71452	5.0	.0	2E24	4.72	.15	2.55	3.12	17.00			4	36	41	.30		.06			
560.0	565.0	71453	5.0	.0	2E2	4.92	.20	2.26	3.38	13.80			4	36	41	.05		.06			
565.0	570.0	71454	5.0	.0	2E2	4.61	.22	1.01	2.36	27.40		.07	4	36	41	.02		.06			
570.0	575.0	71455	5.0	.0	2C7	4.30	.29	1.33	1.81	19.10		.14	15	27	42	.04		.13			
575.0	580.0	71456	5.0	.0	2C7	3.99	.33	.60	.39	12.60		.01	15	27	42	.07		.13			
580.0	585.0	71457	5.0	.0	2C7	4.30	.30	.66	.56	11.10		.14	15	27	42	.02		.13			
585.0	590.0	71458	5.0	.0	2D7	4.45	.05	1.75	7.00	18.30		.07	15	27	42	.03		.13			
590.0	595.0	71459	5.0	.0	2F2	4.45	.05	1.75	7.00	18.30		.07	15	27	42	.03		.13			
595.0	600.0	71460	5.0	.0	2FH4	4.09	.15	1.36	6.23	19.70		.34	5	28	33	.06		.07			
600.0	605.0	71461	5.0	.0	2F0	3.75	.07	5.99	8.44	74.00			5	28	33	.13		.07			
605.0	610.0	71462	5.0	.0	2E4	4.63	.02	3.11	6.33	23.40		.07	5	28	33	.04		.07			
610.0	615.0	71463	5.0	.0	2E4	4.25	.02	3.38	4.72	18.40		.01	5	28	33	.02		.07			
615.0	620.0	71464	5.0	.0	2E4	4.46	.20	3.16	4.81	18.00		.01	6	18	24	.02		.03			
620.0	625.0	71465	5.0	.0	2D0	3.36	.27	2.85	4.88	20.70		.14	6	18	25	.17		.03			
625.0	630.0	71466	5.0	.0	2D0	2.95	.08	2.39	7.14	35.70			6	18	25	22.00		.03			
630.0	635.0	71467	5.0	.0	2A34	2.96	.12	1.49	3.86	30.90			6	18	24	19.00		.03			
635.0	640.0	71468	5.0	.0	2A34	2.69	.02	1.38	3.84	20.80			4	3	7	.21		.03			
640.0	645.0	71469	5.0	.0	2A0	2.90	.07	.56	1.22	11.20			2	2	4	.18		.02			
645.0	649.0	71470	4.0	.0	2A0	2.70	.07	.59	1.62	13.60			2	2	4	.15		.02			
649.0	653.0	71471	4.0	.0	2A4	2.75	.05	.85	3.85	20.40		.06	3	2	5	.13		.03			
653.0	657.0	71472	4.0	.0	2A4	2.90	.06	1.02	4.33	25.60		.27	3	2	5	.13		.03			
657.0	662.0	71473	5.0	.0	2A3	2.96	.09	.74	1.25	11.00			3	2	5	.15		.03			

DDH: 67-12 UTM-N: 8538.0 UTM-E: 14602.0 UTM-ELEV: 4061.0 TOTAL DEPTH: 1006.0 SECTION: 122+020
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

-----DEPTHS-----						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
493.0	499.0	71481	6.0	.0	2C00	3.58	.17	.89	2.88	10.80			6	15	21	.09		.16			
499.0	505.0	71482	6.0	.0	2F40	4.64	.11	6.84	6.00	64.90			6	15	21	1.05		.16			
505.0	510.0	71483	5.0	.0	2B01	2.69	.02	.94	1.23	11.60			6	15	21	2.57		.16			
510.0	515.0	71484	5.0	.0	2B01	2.89	.04	1.89	2.09	33.00			5	8	13	4.31		.21			
515.0	520.0	71485	5.0	.0	2B01	2.68	.03	.70	1.07	14.30			5	8	13	3.82		.21			
520.0	525.0	71486	5.0	.0	2B40	3.25	.06	2.68	2.86	46.30			5	8	13	4.39		.21			
525.0	530.0	71487	5.0	.0	2H49	4.20	.20	7.04	6.20	114.80			5	8	13	3.61		.21			
530.0	535.0	71488	5.0	.0	2D00	3.46	.14	4.94	7.92	84.90			3	7	10	4.98		.14			
535.0	540.0	71489	5.0	.0	2B40	2.83	.05	1.47	3.82	28.10			3	7	10	.65		.14			
540.0	545.0	71490	5.0	.0	2A00	2.76	.06	1.21	2.02	26.90			3	7	10	.90		.14			
545.0	550.0	71491	5.0	.0	2A00	2.72	.02	1.03	2.81	27.80			3	7	10	1.02		.14			
550.0	555.0	71492	5.0	.0	2B0	2.80	.08	1.00	1.97	22.40			6	2	8	.75		.09			
555.0	560.0	71493	5.0	.0	2B0	2.80	.05	.84	1.87	16.80			6	2	8	.57		.09			
560.0	565.0	71494	5.0	.0	2D00	2.92	.04	1.91	4.01	29.10			6	2	8	.31		.09			
565.0	570.0	71495	5.0	.0	2D00	2.99	.02	1.58	3.48	26.00			6	2	8	.06		.09			
570.0	575.0	71496	5.0	.0	2D00	2.91	.03	1.60	3.37	24.30			6	9	16	.17		.12			
575.0	580.0	71497	5.0	.0	2D00	2.79	.05	3.10	5.10	49.20			6	9	16	.19		.12			
580.0	585.0	71498	5.0	.0	2D00	2.85	.08	1.38	6.63	21.80			6	9	16	.09		.12			
585.0	590.0	71499	5.0	.0	2E29	4.25	.41	4.31	5.14	58.40			6	9	16	.04		.12			
590.0	595.0	71500	5.0	.0	2E20	4.74	.09	1.38	2.22	38.00			7	26	34	.02		.15			
595.0	600.0	71501	5.0	.0	2E13	4.59	.17	3.23	4.98	46.80			7	26	34	.02		.15			
600.0	605.0	71502	5.0	.0	2E70	4.49	.08	3.93	6.02	44.80			7	26	34	.05		.15			
605.0	610.0	71503	5.0	.0	2D4	3.73	.13	4.21	9.35	43.70			7	26	34	.10		.15			
610.0	615.0	71504	5.0	.0	2E90	4.55	.21	1.63	1.67	20.10			7	29	36	.02		.20			
615.0	620.0	71505	5.0	.0	2F49	4.62	.30	6.33	10.85	73.70			7	29	36	.02		.20			
620.0	625.0	71506	5.0	.0	2E40	4.54	.15	3.68	5.65	37.50			7	29	36	.05		.20			
625.0	630.0	71507	5.0	.0	2F90	4.49	.22	2.42	2.66	29.80			7	29	36	.25		.20			
630.0	635.0	71508	5.0	.0	2E47	4.43	.17	2.32	2.54	34.50			7	30	38	.03		.16			
635.0	640.0	71509	5.0	.0	2E48	4.40	.56	3.59	3.35	55.90			7	30	38	.27		.16			
640.0	645.0	71510	5.0	.0	2E49	4.60	.65	5.16	6.39	40.60			7	30	38	.02		.16			
645.0	650.0	71511	5.0	.0	2E49	4.96	.27	2.53	4.76	24.90			7	30	38	.02		.16			
650.0	655.0	71512	5.0	.0	2H49	4.12	.53	3.14	5.42	46.00			6	13	20	.07		.07			
655.0	660.0	71513	5.0	.0	2B49	3.15	.25	1.50	5.06	37.50			6	13	20	.22		.07			
660.0	665.0	71514	5.0	.0	2B0	2.70	.06	.90	2.54	25.10			6	13	20	.21		.07			

DDH: 67-30 UTM-N: 8162.6 UTM-E: 14623.6 UTM-ELEV: 4023.7 TOTAL DEPTH: 661.0 SECTION: 124
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
482.8	486.0	71524	3.2	.0	2D3	3.28	.37	5.76	.17	95.10		1.23	4	12	17	.04		.04			
486.0	489.7	71525	3.7	.0	2C3	3.33	.09	.76	1.54	9.40		.34	4	12	17	.03		.04			
489.7	494.0	71526	4.3	.0	2D4	3.26	.21	3.20	8.87	25.30		.69	4	12	17	.06		.04			
494.0	498.7	71527	4.7	.0	2D4	3.38	.19	5.43	8.64	42.60		.27	9	8	18	.05		.20			
498.7	500.0	71528	1.3	.0	2E4	4.88	.05	7.79	6.77	99.20		.14	9	8	18	.04		.20			
500.0	505.0	71529	5.0	.0	2H6	4.37	.25	5.17	4.69	83.40		.07	9	8	18	7.35		.20			
505.0	510.0	71530	5.0	.0	1D49	3.16	.14	3.54	3.66	58.00		.01	9	8	18	2.14		.20			
510.0	514.0	71531	4.0	.0	1D4	2.86	.04	.91	1.53	13.00		.01	9	8	18	2.63		.20			
514.0	517.0	71532	3.0	.0	2A4	3.09	.07	2.20	2.37	30.30		.01	11	13	25	5.98		.33			
517.0	520.0	71533	3.0	.0	2CA	2.83	.04	.69	1.20	11.50		.07	11	13	25	4.94		.33			
520.0	523.6	71534	3.6	.0	2H14	3.75	.20	6.33	6.03	101.10		.07	11	13	25	1.61		.33			
523.6	525.0	71535	1.4	.0	2F64	4.51	.21	5.64	4.90	96.80		.07	11	13	25	5.51		.33			
525.0	529.0	71536	4.0	.0	2H64	4.47	.31	6.43	6.05	96.30		.14	11	13	25	6.47		.33			
529.0	534.0	71537	5.0	.0	2F64	4.59	.12	5.94	5.62	84.70		.21	11	13	25	5.71		.33			
534.0	538.0	71538	4.0	.0	2EH4	4.53	.41	5.01	5.49	71.00		.14	13	10	24	.80		.16			
538.0	540.0	71539	2.0	.0	2H64	3.34	.36	2.38	3.60	33.90		.01	13	10	24	.27		.16			
540.0	545.0	71540	5.0	.0	2H14	4.41	.43	4.86	8.31	57.90		.07	13	10	24	.05		.16			
545.0	550.0	71541	5.0	.0	2D0	3.14	.10	5.78	1.82	113.80		1.10	13	10	24	.12		.16			
550.0	554.0	71542	4.0	.0	2D0	3.10	.07	5.90	1.86	111.90		.07	13	10	24	.20		.16			
554.0	558.0	71543	4.0	.0	2C0	2.92	.08	1.13	2.57	23.40		.01	4	4	9	.25		.05			
558.0	563.0	71544	5.0	.0	2D0	3.01	.11	2.29	4.19	44.30		.07	4	4	9	.42		.05			
563.0	568.0	71545	5.0	.0	2D0	3.12	.23	1.66	5.18	29.00		.07	4	4	9	.28		.05			
568.0	573.0	71546	5.0	.0	2C0	2.87	.08	.73	2.40	12.90			4	4	9	.26		.05			
573.0	578.0	71547	5.0	.0	2C0	2.77	.03	.79	1.87	6.90		.01	3	3	7	.52		.06			
578.0	583.0	71548	5.0	.0	2CA	2.79	.04	.70	1.31	9.70		.07	3	3	7	.36		.06			
583.0	588.0	71549	5.0	.0	2A0	2.94	.06	.84	2.09	12.70		.07	3	3	7	.22		.06			
588.0	593.0	71550	5.0	.0	2A0	2.94	.07	.66	1.53	10.50			3	3	7	.21		.06			
593.0	595.0	71551	2.0	.0	2A0	2.83	.03	.28	.55	4.10			3	3	7	.24		.06			

DDH: 70-12 UTM-N: 8200.3 UTM-E: 14209.7 UTM-ELEV: 4006.7 TOTAL DEPTH: 701.0 SECTION: 122+020
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

-----DEPTHS-----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
541.0	546.0	71560	5.0	.0	2A0	2.95	.08	1.61	2.52	35.30			7	5	13	.28		.10			
546.0	550.0	71561	4.0	.0	2A0	2.96	.11	.76	1.06	12.60			7	5	13	.24		.10			
550.0	554.5	71562	4.5	.0	2A0	2.96	.07	.67	1.25	11.20			7	5	13	.30		.10			
554.5	558.5	71563	4.0	.0	1D41	3.17	.09	2.38	5.61	20.00			7	5	13	.22		.10			
558.5	563.0	71564	4.5	.0	2F4	4.61	.07	7.52	11.65	76.70			5	30	36	.05		.08			
563.0	566.8	71565	3.8	.0	2F4	4.89	.16	6.64	9.00	59.10			5	30	36	.06		.08			
566.8	567.3	71566	.5	.0	2H43	4.60	.49	4.70	6.20	70.00			5	30	36	.03		.08			
567.3	570.9	71567	3.6	.0	2E4	4.71	.14	6.48	8.64	55.30			5	30	36	.14		.08			
570.9	572.8	71568	1.9	.0	2F4	4.84	.09	6.26	11.06	66.50			5	30	36	.03		.08			
572.8	576.0	71569	3.2	.0	2E49	4.99	.39	3.66	6.11	46.30			5	30	36	.03		.08			
576.0	581.0	71570	5.0	.0	2F4	4.88	.15	7.31	7.36	66.20			4	26	31	.04		.06			
581.0	586.0	71571	5.0	.0	2F4	4.99	.12	7.98	11.40	73.40			4	26	31	.04		.06			
586.0	591.0	71572	5.0	.0	2E4	4.75	.15	4.14	7.10	31.10			4	26	31	.03		.06			
591.0	596.0	71573	5.0	.0	2A0	2.90	.14	.86	1.97	22.70			4	26	31	.40		.06			
596.0	601.0	71574	5.0	.0	2A9	3.03	.54	1.63	2.15	50.70			6	5	12	.25		.10			
601.0	604.0	71575	3.0	.0	2A0	2.89	.18	.39	1.14	17.20			6	5	12	.58		.10			

DDH: 70-13 UTM-N: 7561.2 UTM-E: 14814.0 UTM-ELEV: 4011.2 TOTAL DEPTH: 706.0 SECTION:
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
400.0	463.5	71582	63.5	.0	****	2.75															
463.5	467.0	71583	3.5	.0	2B0	2.79	.01	.03	.14	1.50			6	13	19	.31		.15			
467.0	471.0	71584	4.0	.0	2B0	3.32	.25	.88	1.72	13.20			6	13	19	.11		.15			
471.0	475.0	71585	4.0	.0	2D4	3.49	.10	3.28	8.82	25.20			6	13	19	.06		.15			
475.0	479.0	71586	4.0	.0	2G0	4.66	.12	6.46	7.34	81.20			6	13	19	.10		.15			
479.0	483.0	71587	4.0	.0	2A0	2.84	.04	.76	1.72	16.30			6	13	19	.73		.15			
483.0	488.0	71588	5.0	.0	2A0	2.81	.06	.90	2.28	18.20			3	3	7	.45		.05			
488.0	493.0	71589	5.0	.0	2A0	2.84	.05	.39	.64	9.60			3	3	7	.45		.05			
493.0	498.0	71590	5.0	.0	2A0	2.70	.04	.68	1.08	14.60			3	3	7	.60		.05			
498.0	503.0	71591	5.0	.0	2A0	2.72	.04	.51	.82	13.60			3	3	7	.51		.05			
528.0	531.5	71593	3.5	.0	2B4	2.98	.03	6.71	5.15	180.00			3	1	5	.04		.07			
531.5	535.0	71594	3.5	.0	2B0	2.89	.05	5.38	.39	115.50			3	1	5	.14		.07			

05MAR87 !THE IMPERIAL ANVIL!

ASSAY LISTING (DEPTH SEQUENCE) DH015

PAGE: 54

DDH: 71-01 UTM-N: 8118.0 UTM-E: 13975.0 UTM-ELEV: 3967.2 TOTAL DEPTH: 695.0 SECTION: 121+000
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

-----DEPTHS-----		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													S.G. W.R.
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	
614.0	615.5	71622	1.5	.0	2A0	2.90	.06	.83	2.50	14.60			4	4	9	.14		.04		
615.5	616.5	71623	1.0	.0	2H0	3.79	.26	2.93	6.24	58.40			4	4	9	.17		.04		
616.5	620.0	71624	3.5	.0	2A40	2.94	.08	2.40	1.77	47.90			4	4	9	.17		.04		
620.0	625.0	71625	5.0	.0	2A4	2.93	.09	1.78	3.60	39.80			4	4	9	.20		.04		
625.0	630.0	71626	5.0	.0	2A0	2.75	.04	.78	1.75	16.10			4	4	9	.13		.04		

PAGE: 56

DDH: 71-03 UTM-N: 8397.0 UTM-E: 13997.0 UTM-ELEV: 3992.6 TOTAL DEPTH: 645.0 SECTION: 120+000
RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

[illegible]

DDH: 71-05 UTM-N: 7721.0 UTM-E: 14596.0 UTM-ELEV: 4001.5 TOTAL DEPTH: 567.0 SECTION: 126
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
514.0	517.5	71683	3.5	.0	2A0	3.04	.32	1.79	.55	69.30				5 18	23	.14		.21			
517.5	522.5	71684	5.0	.0	2F4	4.05	.18	5.75	6.11	71.60		.27	5 18	23	.64		.21				
522.5	527.5	71685	5.0	.0	2F4	4.61	.18	5.18	5.49	83.60		.27	5 18	23	6.80		.21				
527.5	533.0	71686	5.5	.0	2D0	2.99	.17	2.46	4.08	57.10		.62	5 18	23	1.29		.21				
533.0	536.0	71687	3.0	.0	2DE	3.66	.15	3.98	4.86	76.30		.14	5 7	12	.08		.09				
536.0	540.0	71688	4.0	.0	2D0	2.94	.18	2.56	5.27	36.80		.27	5 7	12	.75		.09				
540.0	544.0	71689	4.0	.0	2D0	3.04	.15	2.06	6.03	39.30		.21	5 7	12	.69		.09				
544.0	549.0	71690	5.0	.0	2A4	2.94	.07	1.83	3.53	36.80		.14	5 7	12	.20		.09				
549.0	555.0	71691	6.0	.0	2A4	2.90	.08	1.67	4.22	34.40		.21	3 3	6	.24		.04				
555.0	560.0	71692	5.0	.0	2A4	2.89	.11	3.54	4.48	60.70		.27	3 3	6	.22		.04				
560.0	565.0	71693	5.0	.0	2A0	2.69	.08	.89	3.09	26.30		.27	3 3	6	.26		.04				

DDH: 72-12 UTM-N: 7366.7 UTM-E: 15116.5 UTM-ELEV: 4018.0 TOTAL DEPTH: 393.0 SECTION: 131
RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS----		-----ASSAYS-----																			
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
320.9	324.5	71835	3.6	.0	2D3	3.30	.08	1.85	3.40	29.60			11	10	22	.73		.24			
324.5	332.0	71836	7.5	.0	****	2.83	.08	.23	.35	6.80			3	3	6	.53		.25			
332.0	334.5	71837	2.5	.0	****	2.68	.06	.33	.73	9.40			4	4	9	.16		.33			

DDH: 72-13 UTM-N: 7571.6 UTM-E: 14463.6 UTM-ELEV: 4002.0 TOTAL DEPTH: 680.0 SECTION: 126
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS----		-----ASSAYS-----																			
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
577.0	582.0	71845	5.0	.0	2C0	2.94	.21	.70	.95	16.10			5	15	20	.30		.12			
582.0	587.0	71846	5.0	.0	2E4	4.07	.19	8.53	6.63	80.40			5	15	20	11.63		.12			
587.0	592.0	71847	5.0	.0	2F4	4.12	.11	5.75	9.60	58.30			.27	5	15	20	5.06	.12			
592.0	597.0	71848	5.0	.0	2B4	3.32	.16	4.87	6.96	56.80			2.61	8	19	27	2.03	.27			
597.0	602.0	71849	5.0	.0	2F4	4.56	.19	6.18	6.55				.21	8	19	27	6.35	.27			
602.0	607.0	71850	5.0	.0	2F4	4.88	.13	6.28	6.53	87.40			.62	8	19	27	6.87	.27			
607.0	612.0	71851	5.0	.0	2F4	4.11	.16	4.97	7.12	74.10			.14	8	19	27	1.70	.27			
612.0	617.0	71852	5.0	.0	2B4	3.30	.25	5.30	5.88	71.20			.21	6	9	16	.77	.12			
617.0	622.0	71853	5.0	.0	2F4	3.98	.34	6.95	9.55	91.20			.21	6	9	16	.31	.12			
622.0	627.0	71854	5.0	.0	2B4	3.04	.07	11.39	2.83	192.80			.27	6	9	16	.10	.12			
627.0	632.0	71855	5.0	.0	1D4	2.73	.08	.80	.25	16.50				6	9	16	.26	.12			
632.0	637.0	71856	5.0	.0	1D4	2.70	.06	.36	.10	5.90				4	4	8	1.07	.05			
637.0	642.0	71857	5.0	.0	2B4	3.04	.11	4.00	3.90	86.10			.07	4	4	8	4.59	.05			
642.0	647.0	71858	5.0	.0	2B0	2.77	.08	.62	1.37	16.20				4	4	8	.27	.05			
666.5	669.0	71860	2.5	.0	2A3	2.81	.10	.81	1.59	15.50				3	6	10	.08	.26			
669.0	673.5	71861	4.5	.0	1D14	2.75	.10	1.81	1.53	17.30			.01	3	6	10	.26	.26			
673.5	678.0	71862	4.5	.0	2A0	2.62	.09	.57	1.50	11.30				3	2	6	.26	.04			

DDH: 72-15 UTM-N: 8569.9 UTM-E: 15442.6 UTM-ELEV: 4188.3 TOTAL DEPTH: 700.0 SECTION: 126
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----								-----ASSAYS-----													
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
>6	611.0	616.0	71870	5.0	.0	2D7	3.42	.10	1.48	4.88	10.50		.07	8 16	25	.04		.03			
4-5	616.0	621.0	71871	5.0	.0	2D0	3.39	.06	1.02	3.05	7.60		.14	8 16	25	.06		.03			
	621.0	626.0	71872	5.0	.0	2D4	4.08	.05	3.97	9.03	20.50		.21	4 14	19	.10		.03			
>6	626.0	631.0	71873	5.0	.0	2D4	3.57	.09	3.14	7.86	22.70		.21	4 14	19	.11		.03			
	631.0	636.0	71874	5.0	.0	2D0	3.25	.16	2.98	5.72	37.10		.07	4 14	19	.21		.03			
	636.0	641.0	71875	5.0	.0	2B4	2.96	.08	1.18	3.49	14.90		.21	4 14	19	.30		.03			
4-5	641.0	646.0	71876	5.0	.0	2B0	2.94	.11	1.52	2.58	23.80		.01	4 14	19	.39		.03			

DDH: 72-16 UTM-N: 8978.1 UTM-E: 15011.7 UTM-ELEV: 4161.8 TOTAL DEPTH: 810.0 SECTION: 122+020
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

-----DEPTHS-----		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
567.0	572.0	71884	5.0	.0	2D37	4.06	.11	5.10	7.08	40.10				1 26	27	10.40		.06			
572.0	577.0	71885	5.0	.0	2G4	4.67	.08	5.98	6.47	67.10				1 26	27	10.42		.06			
577.0	582.0	71886	5.0	.0	2E40	3.96	.03	1.62	3.02	22.90				1 26	27	3.05		.06			
582.0	587.0	71887	5.0	.0	2C3	3.67	.01	.08	.10	4.90				1 26	27	.01		.06			
587.0	592.0	71888	5.0	.0	2C3	3.59	.02	.14	.10	5.60				1 26	27	.05		.06			
592.0	597.0	71889	5.0	.0	2E1	4.17	.03	.56	.33	7.60				4 26	31	.05		.04			
597.0	602.0	71890	5.0	.0	2F40	4.30	.02	3.28	7.53	30.40				4 26	31	.06		.04			
602.0	607.0	71891	5.0	.0	2D48	3.76	.03	4.77	13.30	66.00				4 26	31	.10		.04			
607.0	612.0	71892	5.0	.0	2G40	4.15	.15	3.67	5.91	42.50				4 26	31	2.32		.04			
612.0	617.0	71893	5.0	.0	2E00	4.69	.11	1.88	3.46	15.10				1 32	34	.07		.02			
617.0	622.0	71894	5.0	.0	2E00	4.81	.23	.04	.10	5.90				1 32	34	.04		.02			
622.0	627.0	71895	5.0	.0	2E00	4.97	.19	.06	.14	7.00				1 32	34	.06		.02			
627.0	632.0	71896	5.0	.0	2D40	3.17	.09	2.80	9.50	23.10				1 32	34	.25		.02			
632.0	637.0	71897	5.0	.0	2C00	3.15	.11	1.28	3.10	13.80				1 25	27	.26		.02			
637.0	642.0	71898	5.0	.0	2E4	3.99	.21	2.27	3.65	17.10				1 25	27	.15		.02			
642.0	647.0	71899	5.0	.0	2E18	3.83	.09	.64	1.92	12.60				1 25	27	.16		.02			
647.0	652.0	71900	5.0	.0	2E18	3.66	.10	1.76	1.59	15.40				1 25	27	.09		.02			
652.0	657.0	71901	5.0	.0	2E41	3.84	.14	2.89	1.80	17.20				3 28	31	.07		.17			
657.0	662.0	71902	5.0	.0	2C30	3.50	.05	.34	1.41	6.80				3 28	31	.10		.17			
662.0	667.0	71903	5.0	.0	2E80	4.14	.20	.66	1.34	8.80				3 28	31	.05		.17			
667.0	672.0	71904	5.0	.0	2E89	4.30	.31	1.06	1.88	11.70				3 28	31	.15		.17			
672.0	677.0	71905	5.0	.0	2E89	3.91	.30	.56	1.26	8.80				3 29	32	.04		.13			
677.0	682.0	71906	5.0	.0	2C9	3.59	.50	.12	.58	9.40				3 29	32	.04		.13			
682.0	687.0	71907	5.0	.0	2E8	3.83	.19	.24	.99	5.60				3 29	32	.04		.13			
687.0	692.0	71908	5.0	.0	2E10	4.42	.11	.08	.72	5.50				3 29	32	.05		.13			
692.0	697.0	71909	5.0	.0	2C0	3.52	.17	.84	2.88	8.10				3 18	22	.10		.03			
697.0	702.0	71910	5.0	.0	2C0	3.26	.12	.76	1.72	8.50				3 18	22	.13		.03			
702.0	707.0	71911	5.0	.0	2D0	3.41	.10	1.18	3.05	7.50				3 18	22	.17		.03			
707.0	712.0	71912	5.0	.0	2C0	3.52	.10	.18	1.12	4.20				3 18	22	.10		.03			
712.0	717.0	71913	5.0	.0	2C0	3.71	.17	.12	.87	4.40				6 23	29	.04		.22			
717.0	722.0	71914	5.0	.0	2C9	3.52	.74	.22	1.18	14.60				6 23	29	.05		.22			
722.0	727.0	71915	5.0	.0	2E89	3.66	1.00	.60	.58	16.00				6 23	29	.03		.22			
727.0	732.0	71916	5.0	.0	2E89	3.73	1.50	.18	.50	12.00				6 23	29	.03		.22			
732.0	737.0	71917	5.0	.0	2E89	3.66	1.50	.26	.45	12.60				7 24	32	.02		.17			
737.0	742.0	71918	5.0	.0	2E89	3.96	.73	.12	.42	7.50				7 24	32	.03		.17			
742.0	747.0	71919	5.0	.0	2E89	3.96	.75	.30	1.41	8.40				7 24	32	.02		.17			
747.0	752.0	71920	5.0	.0	2E89	3.87	.49	.50	.80	6.90				7 24	32	.03		.17			
752.0	757.0	71921	5.0	.0	2E89	3.98	.60	1.62	1.61	12.60				4 28	33	.02		.13			
757.0	762.0	71922	5.0	.0	2E81	4.28	.30	.28	1.65	5.50				4 28	33	.01		.13			
762.0	767.0	71923	5.0	.0	2E81	4.05	.26	.74	2.07	5.60				4 28	33	.02		.13			
767.0	772.0	71924	5.0	.0	2D39	3.97	.06	1.76	7.12	6.60				4 28	33	.08		.13			
772.0	777.0	71925	5.0	.0	2C3	3.88	.04	.44	1.70	3.90				4 16	20	.04		.04			
777.0	782.0	71926	5.0	.0	2D3	3.87	.05	3.90	8.82	19.90				4 16	20	.09		.04			
782.0	787.0	71927	5.0	.0	2Q9?	3.15	.14	1.97	5.94	20.00				4 16	20	.22		.04			
787.0	792.0	71928	5.0	.0	1D40	2.79	.05	.32	1.08	10.80				4 16	20	.30		.04			

DDH: 72004 UTM-N: 8801.1 UTM-E: 13597.3 UTM-ELEV: 4036.2 TOTAL DEPTH: 600.0 SECTION:
 RFE: RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
509.0	511.5	71701	2.5	.0	2J4	3.79	.13	5.04	11.90	77.80			4	4	9	.11		.05			
511.5	516.5	71702	5.0	.0	2C0	2.81	.05	1.69	3.67	34.00			4	4	9	.14		.05			
516.5	521.0	71703	4.5	.0	2B4	2.69	.04	1.41	4.73	24.60			4	4	9	.10		.05			
521.0	526.1	71704	5.1	.0	2B44	2.85	.06	3.53	7.73	60.90			4	4	9	.08		.05			

DDH: 72007 UTM-N: 9804.6 UTM-E: 13996.7 UTM-ELEV: 4040.2 TOTAL DEPTH: 437.0 SECTION:
 RFE: RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

---DEPTHS---		-----ASSAYS-----																			
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
90.0	95.0	71735	5.0	.0	****	.50	.23	.60	.60												
95.0	100.0	71736	5.0	.0	****	.50	.24	5.70	6.20												
100.0	105.0	71737	5.0	.0	****	.50		3.50	5.70												
105.0	110.0	71738	5.0	.0	****	.50	.17	6.00	6.10												
110.0	115.0	71739	5.0	.0	****	.50	.01	4.30	6.10												
115.0	120.0	71740	5.0	.0	****	.50	.23	3.80	4.50												
120.0	125.0	71741	5.0	.0	****	.50	.32	5.00	7.60												
125.0	130.0	71742	5.0	.0	****	.50	.02	5.60	8.80												
130.0	135.0	71743	5.0	.0	****	.50	.12	7.60	8.00												
135.0	140.0	71744	5.0	.0	****	.50	.21	6.70	6.00												
140.0	145.0	71745	5.0	.0	****	.50	.24	4.60	5.60												
145.0	150.0	71746	5.0	.0	****	.50	.22	5.30	5.70												
150.0	155.0	71747	5.0	.0	****	.50	.13	7.00	6.50												
155.0	160.0	71748	5.0	.0	****	.50	.16	6.70	5.70												
160.0	165.0	71749	5.0	.0	****	.50	.10	6.30	7.70												
165.0	170.0	71750	5.0	.0	****	.50	.12	5.30	5.50												
170.0	175.0	71751	5.0	.0	****	.50	.18	6.60	6.30												
175.0	180.0	71752	5.0	.0	****	.50	.17	5.40	6.10												
180.0	185.0	71753	5.0	.0	****	.50	.14	5.90	6.50												
185.0	190.0	71754	5.0	.0	****	.50	.14	5.00	6.90												
190.0	195.0	71755	5.0	.0	****	4.26	.07	.81	.39	12.00			2	34	37	.23		.02			
195.0	200.0	71756	5.0	.0	****	3.83	.03	.21	.18	5.00			2	34	37	.07		.02			
200.0	205.0	71757	5.0	.0	****	4.86	.37	2.35	2.15	21.00			2	34	37	.02		.02			
205.0	210.0	71758	5.0	.0	****	4.97	.39	2.21	2.60	19.00			2	34	37	.16		.02			
210.0	215.0	71759	5.0	.0	****	4.89	.36	.87	.16	12.00			2	37	40	.03		.02			
215.0	220.0	71760	5.0	.0	****	4.33	.19	.72	.21	11.00			2	37	40	.03		.02			
220.0	225.0	71761	5.0	.0	****	4.58	.06	.88	.13	11.00			2	37	40	.02		.02			
225.0	230.0	71762	5.0	.0	****	4.38	.07	.65	.09	10.00			2	37	40	.02		.02			
230.0	235.0	71763	5.0	.0	****	4.18	.11	2.24	.12	23.00			2	35	37	.02		.02			
235.0	240.0	71764	5.0	.0	****	4.39	.04	.92	.09	11.00			2	35	37	.05		.02			
240.0	245.0	71765	5.0	.0	****	4.70	.13	2.14	2.28	23.00			2	35	37	.04		.02			
245.0	250.0	71766	5.0	.0	****	4.38	.02	.44	.47	7.00			2	35	37	.02		.02			
250.0	255.0	71767	5.0	.0	****	4.11	.04	.27	.17	5.00			2	25	28	.04		.06			
255.0	260.0	71768	5.0	.0	****	3.31	.05	.20	.12	6.00			2	25	28	.22		.06			
260.0	265.0	71769	5.0	.0	****	4.20	.18	1.35	.55	19.00			2	25	28	.54		.06			
265.0	270.0	71770	5.0	.0	****	4.55	.16	4.46	4.88	57.70			2	25	28	12.71		.06			
270.0	275.0	71771	5.0	.0	****	4.64	.24	5.00	6.15	51.10			6	28	35	19.21		.16			
275.0	280.0	71772	5.0	.0	****	4.14	.21	2.50	3.05	55.80			6	28	35	.29		.16			
280.0	285.0	71773	5.0	.0	****	4.10	.59	.38	1.82	7.90			6	28	35	.06		.16			
285.0	290.0	71774	5.0	.0	****	4.48	.55	.56	1.98	7.00			6	28	35	.03		.16			
290.0	295.0	71775	5.0	.0	****	4.48	.78	.36	1.46	7.40			7	35	42	.02		.13			
295.0	300.0	71776	5.0	.0	****	4.42	.44	1.88	2.67	9.40			7	35	42	.03		.13			
300.0	305.0	71777	5.0	.0	****	4.57	.43	.92	3.19	7.80			7	35	42	.03		.13			
305.0	310.0	71778	5.0	.0	****	4.67	.50	.78	2.90	8.10			7	35	42	.02		.13			
310.0	315.0	71779	5.0	.0	****	4.48	.20	3.00	7.42	11.80			4	36	40	.02		.09			
315.0	320.0	71780	5.0	.0	****	4.85	.05	3.81	7.96	13.50			4	36	40	.01		.09			
320.0	325.0	71781	5.0	.0	****	5.02	.08	2.07	1.60	8.60			4	36	40	.02		.09			
325.0	330.0	71782	5.0	.0	****	4.61	.30	.60	1.90	6.30			4	36	40	.11		.09			
330.0	335.0	71783	5.0	.0	****	4.24	.23	1.08	3.56	7.00			7	30	37	.08		.12			
335.0	340.0	71784	5.0	.0	****	4.15	.17	.22	2.69	4.90			7	30	37	.03		.12			
340.0	345.0	71785	5.0	.0	****	4.28	.25	.84	5.28	6.90			7	30	37	.02		.12			

DDH: 72007 UTM-N: 9804.6 UTM-E: 13996.7 UTM-ELEV: 4040.2 TOTAL DEPTH: 437.0 SECTION:
 RFE: RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS---						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
345.0	350.0	71786	5.0	.0	****	4.42	.17	4.90	9.16	16.80			7	30	37	.02		.12			
350.0	355.0	71787	5.0	.0	****	4.32	.20	2.30	2.89	8.70			7	33	41	.02		.13			
355.0	360.0	71788	5.0	.0	****	4.52	.21	.98	2.94	6.20			7	33	41	.02		.13			
360.0	365.0	71789	5.0	.0	****	4.63	.26	.74	2.79	5.00			7	33	41	.02		.13			
365.0	370.0	71790	5.0	.0	****	4.62	.27	.50	1.62	5.50			7	33	41	.03		.13			
370.0	375.0	71791	5.0	.0	****	4.78	.30	.62	1.99	6.40			3	38	41	.05		.04			
375.0	380.0	71792	5.0	.0	****	4.88	.23	1.62	3.37	8.00			3	38	41	.01		.04			
380.0	385.0	71793	5.0	.0	****	5.21	.36	3.31	4.97	14.00			3	38	41	.02		.04			
385.0	390.0	71794	5.0	.0	****	4.93	.50	2.92	5.42	16.00			3	38	41	.01		.04			
390.0	395.0	71795	5.0	.0	****	4.79	.45	2.38	5.83	15.00			3	20	24	.01		.03			
395.0	400.0	71796	5.0	.0	****	4.63	.34	2.79	7.13	17.00			3	20	24	.03		.03			
400.0	405.0	71797	5.0	.0	****	4.29	.19	4.43	6.99	42.00			3	20	24	.22		.03			
405.0	410.0	71798	5.0	.0	****	3.27	.11	2.03	5.14	22.00			3	20	24	.26		.03			
410.0	415.0	71799	5.0	.0	****	3.30	.11	2.02	3.94	19.00			5	7	12	.23		.03			
415.0	420.0	71800	5.0	.0	****	3.05	.09	3.78	7.83	28.00			5	7	12	.28		.03			
420.0	425.0	71801	5.0	.0	****	3.34	.07	7.46	15.29	71.00			5	7	12	.07		.03			
425.0	430.0	71802	5.0	.0	****	3.33	.13	3.66	11.72	34.00			5	7	12	.08		.03			
430.0	437.0	71803	7.0	.0	****	2.92	.07	.82	3.14	15.00			4	8	13	.12		.02			

PAGE: 67

[illegible]

DDH: 73-01 UTM-N: 9684.3 UTM-E: 14711.2 UTM-ELEV: 4182.6 TOTAL DEPTH: 549.0 SECTION: 117+000
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

-----DEPTHS-----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
279.0	284.0	71933	5.0	.0	2E42	3.54	.08	2.43	3.34	27.50			4	15	20	.27		.07			
284.0	289.0	71934	5.0	.0	2E42	3.96	.18	1.98	2.03	40.20			4	15	20	2.23		.07			
289.0	294.0	71935	5.0	.0	1D4	2.65	.04	.05	.06	2.60			4	15	20	.28		.07			
294.0	299.0	71936	5.0	.0	1D4	2.77	.04	.07	.08	5.40			4	1	6	.10		.06			
299.0	304.0	71937	5.0	.0	0Q9(	3.13	.24	5.50	.14	210.00			4	1	6	.05		.06			
304.0	309.0	71938	5.0	.0	1D4	2.86	.13	3.99	.22	92.70			4	1	6	3.53		.06			
309.0	313.0	71939	4.0	.0	1D4(	2.82	.21	1.84	1.88	55.50			4	1	6	.03		.06			
313.0	319.0	71940	6.0	.0	2G4(	3.60	.11	4.57	5.89	232.00			6	8	14	13.06		.08			
319.0	324.0	71941	5.0	.0	2H4(	3.79	.24	2.29	15.40	42.50			6	8	14	.36		.08			
324.0	329.0	71942	5.0	.0	2L14	2.92	.05	2.03	4.05	30.40			6	8	14	3.36		.08			

DDH: 73-02 UTM-N: 9254.1 UTM-E: 14275.2 UTM-ELEV: 4060.2 TOTAL DEPTH: 700.0 SECTION: 117+000
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

-----DEPTHS-----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
375.0	380.0	71948	5.0	.0	2C0	2.94	.12	.54	1.08	11.70				5 15	20	.17		.15			
380.0	385.0	71949	5.0	.0	2D00	3.20	.10	4.06	5.77	42.30				5 15	20	.27		.15			
385.0	390.0	71950	5.0	.0	2F00	4.54	.18	4.23	5.77	49.30				5 15	20	2.72		.15			
390.0	395.0	71951	5.0	.0	2G48	4.41	.14	4.59	6.46	60.90				5 22	28	17.22		.32			
395.0	400.0	71952	5.0	.0	2G48	4.84	.16	5.63	7.11	68.90				5 22	28	7.43		.32			
400.0	405.0	71953	5.0	.0	2F48	4.10	.09	4.45	4.92	53.70				5 22	28	.99		.32			

PAGE: 71

[illegible]

DDH: 73028 UTM-N: 9176.4 UTM-E: 13801.5 UTM-ELEV: 3948.2 TOTAL DEPTH: 330.0 SECTION:
 RFE: RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
235.0	240.0	72001	5.0	.0	****	3.00	.19	.46	.79	9.00			9	15	25	.09		.13			
240.0	245.0	72002	5.0	.0	****	2.88	.04	2.94	3.46	22.00			9	15	25	.13		.13			
245.0	250.0	72003	5.0	.0	****	3.47	.08	2.32	4.43	31.00			9	15	25	.09		.13			
250.0	255.0	72004	5.0	.0	****	4.30	.26	4.93	7.77	58.00			9	15	25	.46		.13			
255.0	260.0	72005	5.0	.0	****	4.61	.24	5.60	8.05	67.00			9	15	25	.14		.13			
260.0	265.0	72006	5.0	.0	****	4.63	.19	6.93	8.82	77.00			7	11	18	1.65		.11			
265.0	270.0	72007	5.0	.0	****	3.23	.22	3.70	7.44	51.00			7	11	18	.26		.11			
270.0	275.0	72008	5.0	.0	****	3.23	.08	3.41	7.12	59.00			7	11	18	.28		.11			
275.0	280.0	72009	5.0	.0	****	3.03	.08	1.66	4.35	34.00			7	11	18	.24		.11			
280.0	285.0	72010	5.0	.0	****	3.01	.12	1.95	3.00	36.00			5	4	9	.24		.03			
285.0	290.0	72011	5.0	.0	****	3.03	.08	1.86	4.79	32.00			5	4	9	.29		.03			
290.0	295.0	72012	5.0	.0	****	3.13	.12	2.12	5.46	38.00			5	4	9	.18		.03			
295.0	300.0	72013	5.0	.0	****	2.69	.05	.82	1.94	20.00			5	4	9	.30		.03			
300.0	305.0	72014	5.0	.0	****	2.81	.04	1.51	2.73	28.00			2	2	5	.18		.05			
305.0	310.0	72015	5.0	.0	****	2.81	.04	.01	.04	2.00			2	2	5	.23		.05			
310.0	315.0	72016	5.0	.0	****	2.74	.05	.87	1.60	12.00			2	2	5	.20		.05			
315.0	320.0	72017	5.0	.0	****	2.92	.09	2.31	4.06	52.00			2	2	5	.29		.05			
320.0	325.0	72018	5.0	.0	****	2.83	.06	1.05	2.19	24.00			3	2	6	.35		.05			
325.0	330.0	72019	5.0	.0	****	2.81	.05	.52	1.18	9.00			3	2	6	.27		.05			

DDH: 73029 UTM-N: 9956.6 UTM-E: 14589.8 UTM-ELEV: 4120.0 TOTAL DEPTH: 307.0 SECTION:
 RFE: RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
147.0	152.0	72023	5.0	.0	****	3.21	.24	1.44	2.03	40.00			7	9	16	1.00		.07			
152.0	157.0	72024	5.0	.0	****	3.66	.15	.77	2.31	24.00			4	20	24	.05		.06			
157.0	162.0	72025	5.0	.0	****	3.45	.13	.36	.91	12.00			5	16	22	.06		.06			
212.0	217.0	72028	5.0	.0	****	3.63	.41	1.95	.21	56.00			9	16	26	.10		.07			
217.0	222.0	72029	5.0	.0	****	3.31	.25	.82	.19	30.00			9	7	17	.15		.10			
222.0	227.0	72030	5.0	.0	****	3.55	.19	.15	1.31	15.00			5	18	23	.09		.06			
227.0	232.0	72031	5.0	.0	****	2.91	.03	.17	.16	10.00			3	1	5	.19		.07			
232.0	237.0	72032	5.0	.0	****	3.59	.20	.03	.40	7.00			5	19	25	.08		.05			
237.0	242.0	72033	5.0	.0	****	2.76	.16	.31	.25	10.00			5	4	10	.16		.05			
242.0	247.0	72034	5.0	.0	****	3.38	.12	1.75	3.70	24.00			6	10	17	.12		.05			
247.0	252.0	72035	5.0	.0	****	3.35	.04	1.97	4.94	22.00			2	13	15	.17		.04			
252.0	257.0	72036	5.0	.0	****	3.20	.11	1.98	3.85	24.00			3	7	11	.17		.05			
257.0	262.0	72037	5.0	.0	****	3.27	.08	4.75	6.29	66.00			3	9	12	.13		.04			
262.0	267.0	72038	5.0	.0	****	3.00	.05	.77	.34	32.00			3	5	8	.13		.06			
267.0	272.0	72039	5.0	.0	****	3.42	.05	3.72	7.41	31.00			2	12	15	.08		.03			
272.0	277.0	72040	5.0	.0	****	3.22	.18	1.12	1.32	20.00			5	10	16	.08		.03			
277.0	282.0	72041	5.0	.0	****	2.94	.18	.62	.96	13.00			5	6	12	.14		.05			
282.0	287.0	72042	5.0	.0	****	3.91	.10	3.67	12.45	32.00			4	15	20	.04		.05			
287.0	292.0	72043	5.0	.0	****	3.46	.07	6.08	9.38	49.00			4	9	14	.08		.03			
292.0	297.0	72044	5.0	.0	****	3.68	.22	2.16	8.79	24.00			9	13	22	.07		.04			
297.0	302.0	72045	5.0	.0	****	3.11	.18	2.55	4.37	41.00			7	2	9	.25		.04			
302.0	307.0	72046	5.0	.0	****	3.07	.12	1.26	2.16	29.00			5	5	11	.12		.06			

DDH: 74-01 UTM-N: 9701.5 UTM-E: 14908.2 UTM-ELEV: 4112.8 TOTAL DEPTH: 523.0 SECTION: 118+000
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

-----DEPTHS-----						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
314.0	319.0	72052	5.0	.0	2D4(	3.00	.10	2.97	8.85	53.80			5	11	16	.21		.13			
319.0	324.0	72053	5.0	.0	1D4(	3.17	.03	.66	.68	16.50			5	11	16	.09		.13			
324.0	329.0	72054	5.0	.0	2D4(	3.07	.07	6.51	3.18	73.00			4	8	13	.11		.11			
358.0	363.0	72056	5.0	.0	2C7&	3.32	.37	1.92	.70	23.50			6	16	22	.10		.07			
363.0	368.0	72057	5.0	.0	2C7(	3.38	.17	1.78	3.00	23.10			6	16	22	.15		.07			
368.0	373.0	72058	5.0	.0	2C3(	3.82	.11	1.78	2.37	17.20			6	16	22	.08		.07			
373.0	378.0	72059	5.0	.0	2C3	3.02	.18	1.12	1.76	18.50			6	16	22	.16		.07			
391.0	396.0	72061	5.0	.0	2A4(	3.21	.10	2.94	6.32	27.00			3	15	18	.11		.07			
396.0	401.0	72062	5.0	.0	2A4	3.40	.05	4.08	10.00	32.20			3	15	18	.22		.07			
401.0	406.0	72063	5.0	.0	2D3&	3.30	.10	2.00	4.93	29.70			3	15	18	.13		.07			
406.0	411.0	72064	5.0	.0	2A4	3.25	.03	2.73	7.23	22.40			1	15	16	.17		.02			
411.0	416.0	72065	5.0	.0	2A4	3.18	.05	4.70	7.61	50.10			1	15	16	.16		.02			
416.0	421.0	72066	5.0	.0	2A4	3.36	.02	1.94	7.40	19.50			1	15	16	.19		.02			
421.0	426.0	72067	5.0	.0	2A4	3.35	.02	2.42	5.70	20.50			1	15	16	.15		.02			
426.0	431.0	72068	5.0	.0	2A4	3.45	.03	1.78	5.22	23.30			1	17	19	.14		.02			
431.0	436.0	72069	5.0	.0	2A4	3.29	.02	.94	3.26	16.10			1	17	19	.17		.02			
436.0	441.0	72070	5.0	.0	2A0	3.23	.03	.58	1.94	13.70			1	17	19	.16		.02			
441.0	446.0	72071	5.0	.0	2A4	3.34	.02	1.56	4.36	23.10			1	17	19	.13		.02			
446.0	451.0	72072	5.0	.0	2A0	3.08	.03	.52	.72	24.80			1	18	19	.22		.02			
451.0	456.0	72073	5.0	.0	2A0	3.23	.04	.34	1.84	9.10			1	18	19	.19		.02			
456.0	461.0	72074	5.0	.0	2A0	3.14	.06	.50	1.80	13.50			1	18	19	.18		.02			
461.0	466.0	72075	5.0	.0	2A0	3.28	.03	.38	.98	13.50			1	18	19	.14		.02			
466.0	471.0	72076	5.0	.0	2A0	3.19	.03	.54	1.82	17.20			2	22	24	.23		.03			
471.0	476.0	72077	5.0	.0	2A4	3.63	.02	2.59	6.42	19.50			2	22	24	.16		.03			
476.0	481.0	72078	5.0	.0	2F0(	4.76	.01	2.28	5.61	16.30			2	22	24	.04		.03			
481.0	486.0	72079	5.0	.0	2D4(	4.08	.02	5.07	10.47	37.10			2	22	24	.05		.03			
486.0	491.0	72080	5.0	.0	2D0	3.34	.06	2.35	5.70	27.70			2	22	24	.13		.03			

DDH: 74-02 UTM-N: 9032.6 UTM-E: 13965.5 UTM-ELEV: 3965.5 TOTAL DEPTH: 474.0 SECTION: 117+000
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

-----DEPTHS-----						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
272.0	277.0	72084	5.0	.0	2D0	2.97	.09	1.71	3.99	28.70			3	4	8	.21		.04			
277.0	282.0	72085	5.0	.0	2D0	2.93	.10	1.76	4.59	42.00			3	4	8	.22		.04			
282.0	287.0	72086	5.0	.0	2D0	2.93	.24	1.72	3.17	45.20			3	4	8	.23		.04			
287.0	292.0	72087	5.0	.0	2E40	3.62	.13	5.80	6.92	68.80			7	23	30	.35		.19			
292.0	297.0	72088	5.0	.0	2F4	4.29	.10	5.45	8.36	56.40			7	23	30	.07		.19			
297.0	302.0	72089	5.0	.0	2F4	4.41	.08	6.41	8.72	58.90			7	23	30	.14		.19			
302.0	307.0	72090	5.0	.0	2F40	4.33	.18	7.22	7.32	60.90			7	23	30	.89		.19			

DDH: 74-07 UTM-N: 9398.7 UTM-E: 15001.9 UTM-ELEV: 4138.5 TOTAL DEPTH: 777.0 SECTION: 120+000
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

-----DEPTHS-----						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
404.0	409.0	72236	5.0	.0	2D00	3.36	.10	6.99	3.73	126.50				5	9	14	.18				.10
409.0	414.0	72237	5.0	.0	2D00	3.06	.06	3.29	3.25	35.30				5	9	14	.09				.10
414.0	419.0	72238	5.0	.0	1D40	2.87	.08	1.46	.64	36.30				5	9	14	.12				.10
419.0	424.0	72239	5.0	.0	2C30	3.09	.13	4.28	1.72	113.80				5	9	14	.13				.10
424.0	429.0	72240	5.0	.0	2D45	3.43	.21	4.10	4.40	49.40				5	9	14	.11				.10
429.0	434.0	72241	5.0	.0	2C30	3.53	.09	1.76	2.48	16.50				3	21	24	.10				.05
434.0	439.0	72242	5.0	.0	2C30	3.35	.27	1.06	1.00	20.40				3	21	24	.07				.05
439.0	444.0	72243	5.0	.0	2C30	3.65	.11	3.35	3.98	32.30				3	21	24	.10				.05
444.0	449.0	72244	5.0	.0	2C3&	3.62	.11	.73	1.84	7.20				3	21	24	.03				.05
449.0	454.0	72245	5.0	.0	2C3&	3.71	.12	1.54	2.22	12.60				3	24	28	.07				.06
454.0	459.0	72246	5.0	.0	2C39	4.03	.21	.37	.96	6.00				3	24	28	.02				.06
459.0	464.0	72247	5.0	.0	2C3	3.77	.07	1.02	1.86	10.30				3	24	28	.06				.06
464.0	469.0	72248	5.0	.0	2C30	3.05	.26	1.58	2.01	23.90				3	24	28	.09				.06
469.0	474.0	72249	5.0	.0	2C30	3.20	.14	1.23	3.53	14.90				3	18	21	.15				.03
474.0	479.0	72250	5.0	.0	2D00	3.26	.10	1.46	3.39	14.40				3	18	21	.16				.03
479.0	484.0	72251	5.0	.0	2C3	3.40	.07	.60	1.55	9.80				3	18	21	.12				.03
484.0	489.0	72252	5.0	.0	2D00	3.05	.08	1.10	3.52	9.00				3	18	21	.13				.03
489.0	494.0	72253	5.0	.0	2C0	3.50	.09	.09	1.27	3.60				2	21	23	.09				.01
494.0	499.0	72254	5.0	.0	2A30	3.37	.07	.20	1.22	6.20				2	21	23	.10				.01
499.0	504.0	72255	5.0	.0	2A43	3.19	.08	1.56	4.31	14.10				2	21	23	.14				.01
504.0	509.0	72256	5.0	.0	2A43	3.43	.09	1.39	2.97	13.60				2	21	23	.10				.01
509.0	514.0	72257	5.0	.0	2C30	3.45	.21	.12	1.24	6.80				2	24	26	.09				.02
514.0	519.0	72258	5.0	.0	2A3	3.45	.09	.78	1.77	9.40				2	24	26	.11				.02
519.0	524.0	72259	5.0	.0	2A30	3.73	.09	.26	1.24	8.50				2	24	26	.07				.02
524.0	529.0	72260	5.0	.0	2C30	3.58	.08	2.14	3.63	12.60				2	24	26	.07				.02
529.0	534.0	72261	5.0	.0	2C30	3.97	.14	1.11	2.32	8.10				2	27	29	.03				.02
534.0	539.0	72262	5.0	.0	2C39	3.76	.31	.63	2.35	7.90				2	27	29	.04				.02
539.0	544.0	72263	5.0	.0	2C39	3.65	.21	.16	.75	5.10				2	27	29	.06				.02
544.0	549.0	72264	5.0	.0	2C3	3.45	.12	.10	.95	6.10				2	27	29	.05				.02
549.0	554.0	72265	5.0	.0	2C30	3.91	.14	.19	2.34	4.90				1	31	33	.03				.01
554.0	559.0	72266	5.0	.0	2C3	4.00	.17	.07	1.85	4.40				1	31	33	.03				.01
559.0	564.0	72267	5.0	.0	2C3	3.90	.07	.10	1.20	4.30				1	31	33	.06				.01
564.0	569.0	72268	5.0	.0	2C3	4.02	.05	.37	2.17	7.00				1	31	33	.03				.01
569.0	574.0	72269	5.0	.0	2A13	3.33	.10	1.34	2.18	18.60				2	19	22	.12				.02
574.0	579.0	72270	5.0	.0	2D00	3.61	.10	3.23	3.20	22.20				2	19	22	.10				.02
579.0	584.0	72271	5.0	.0	2C0	3.38	.07	.82	2.52	8.50				2	19	22	.17				.02
584.0	589.0	72272	5.0	.0	2C0	3.21	.08	.44	1.69	9.90				2	19	22	.17				.02
589.0	594.0	72273	5.0	.0	2C0	3.50	.08	.37	1.95	8.10				3	19	22	.15				.02
594.0	599.0	72274	5.0	.0	2D43	3.45	.03	3.46	7.43	17.20				3	19	22	.10				.02
599.0	604.0	72275	5.0	.0	2D43	3.56	.07	2.40	6.57	18.60				3	19	22	.13				.02
604.0	609.0	72276	5.0	.0	2F40	3.84	.05	3.78	9.47	28.70				3	19	22	.08				.02
609.0	614.0	72277	5.0	.0	2D40	3.86	.05	4.09	9.94	31.60				2	16	18	.10				.03
614.0	619.0	72278	5.0	.0	2D40	4.09	.03	6.21	14.70	43.70				2	16	18	.08				.03
619.0	624.0	72279	5.0	.0	2F40	3.86	.04	4.41	8.85	32.70				2	16	18	.13				.03
624.0	629.0	72280	5.0	.0	2C00	2.78	.03	.55	.12	22.10				2	16	18	.15				.03
629.0	634.0	72281	5.0	.0	1D4	2.73	.09	.38	1.24	7.60				4	5	10	.17				.04
634.0	639.0	72282	5.0	.0	1D4	2.66	.14	1.75	.08	61.30				4	5	10	.11				.04
639.0	644.0	72283	5.0	.0	1D40	2.76	.21	.67	3.50	15.90				4	5	10	.21				.04
644.0	649.0	72284	5.0	.0	2C00	2.84	.13	.51	2.11	7.60				4	5	10	.15				.04
649.0	654.0	72285	5.0	.0	2D00	2.79	.08	2.23	2.91	43.40				3	3	6	.26				.02
654.0	659.0	72286	5.0	.0	2C00	2.72	.09	.95	3.10	28.30				3	3	6	.34				.02

DDH: 74-07 UTM-N: 9398.7 UTM-E: 15001.9 UTM-ELEV: 4138.5 TOTAL DEPTH: 777.0 SECTION: 120+000
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

-----DEPTHS----						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
659.0	664.0	72287	5.0	.0	2C00	2.75	.13	.65	2.24	13.50				3	3	6	.30		.02		
664.0	669.0	72288	5.0	.0	2D00	2.85	.05	2.80	6.42	33.50				3	3	6	.26		.02		
669.0	674.0	72289	5.0	.0	2D4	2.87	.08	3.74	7.31	38.30				3	3	7	.17		.04		
674.0	679.0	72290	5.0	.0	2D0	2.77	.12	1.61	2.78	23.10				3	3	7	.18		.04		
679.0	684.0	72291	5.0	.0	1D40	2.83	.10	.50	2.32	14.20				3	3	7	.19		.04		
684.0	689.0	72292	5.0	.0	2D4	2.61	.13	4.03	7.23	51.60				3	3	7	.12		.04		
689.0	694.0	72293	5.0	.0	2D40	2.97	.08	4.59	9.52	71.00				5	5	10	.15		.07		
694.0	699.0	72294	5.0	.0	1D40	2.85	.09	1.13	2.35	21.20				5	5	10	.39		.07		
699.0	704.0	72295	5.0	.0	2D40	3.33	.06	2.02	7.33	56.10				5	5	10	.08		.07		
704.0	709.0	72296	5.0	.0	2D40	3.18	.17	3.82	10.05	60.90				5	5	10	.14		.07		
709.0	714.0	72297	5.0	.0	2D0&	2.79	.07	1.59	5.33	25.10				3	3	7	.19		.05		
714.0	719.0	72298	5.0	.0	2D4&	2.81	.07	3.36	7.58	54.20				3	3	7	.14		.05		
719.0	724.0	72299	5.0	.0	2D4&	3.00	.08	3.40	7.60	41.60				3	3	7	.12		.05		
724.0	729.0	72300	5.0	.0	1D40	2.82	.02	.29	.10	7.10				3	3	7	.27		.05		
729.0	734.0	72301	5.0	.0	1D40	2.96	.07	1.61	2.45	29.50				3	3	7	.22		.05		

DDH: 74-08 UTM-N: 8002.8 UTM-E: 14796.3 UTM-ELEV: 4017.8 TOTAL DEPTH: 576.0 SECTION: 126
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
395.0	400.0	72307	5.0	.0	2ED	3.59	.17	1.12	4.60	19.30		.07	5	20	26	.14		.07			
400.0	405.0	72308	5.0	.0	2DE4	4.12	.14	5.69	12.94	68.30		.14	5	20	26	.08		.07			
405.0	410.0	72309	5.0	.0	2E14	4.20	.33	5.23	8.03	75.10		.14	5	20	26	.30		.07			
410.0	415.0	72310	5.0	.0	2D0	3.77	.14	1.28	3.13	27.60		.21	2	22	24	.08		.02			
415.0	420.0	72311	5.0	.0	2EC	3.81	.22	.15	.14	10.90		.14	2	22	24	.07		.02			
420.0	425.0	72312	5.0	.0	2C0	3.45	.29	1.01	.14	30.20		.48	2	22	24	.13		.02			
425.0	430.0	72313	5.0	.0	2C0	3.01	.39	.51	.18	20.80			2	21	23	.10		.02			
430.0	435.0	72314	5.0	.0	2CF	3.84	.20	3.31	3.36	42.30		.27	4	22	26	.14		.28			
435.0	440.0	72315	5.0	.0	1D/2E	3.86	.17	5.44	4.39	63.60		.41	4	22	26	.42		.28			
440.0	445.0	72316	5.0	.0	2ED4	3.68	.20	5.93	4.29	65.70		.41	4	22	26	.71		.28			
445.0	450.0	72317	5.0	.0	2GD4	4.31	.13	6.05	5.76	82.00			4	22	26	12.11		.28			
450.0	455.0	72318	5.0	.0	2B0	2.81	.04	.99	1.04	13.90			4	10	14	4.41		.17			
455.0	460.0	72319	5.0	.0	2B0	2.69	.04	.59	.72	10.10			4	10	14	3.97		.17			
460.0	465.0	72320	5.0	.0	2B0	2.77	.04	.40	.48	7.00			4	10	14	2.18		.17			
465.0	470.0	72321	5.0	.0	2B4	4.67	.31	5.26	4.97	76.50			4	10	14	.09		.17			
470.0	475.0	72322	5.0	.0	2B0	2.69	.03	.28	.39	5.50		.07	4	4	9	2.26		.22			
482.0	487.0	72324	5.0	.0	2DB	3.12	.08	4.64	4.21	70.30		.07	4	4	9	8.21		.22			
487.0	492.0	72325	5.0	.0	2D0	3.01	.12	3.38	3.37	53.40		.07	21	16	37	4.47		.16			
492.0	497.0	72326	5.0	.0	2H4	4.25	.29	4.74	7.81	69.60		.07	21	16	37	1.37		.16			
497.0	502.0	72327	5.0	.0	2H4	4.33	.35	2.99	3.53	40.50		.01	21	16	37	.05		.16			
502.0	507.0	72328	5.0	.0	2EG	4.63	.21	2.40	3.22	34.60		.01	21	16	37	1.27		.16			
507.0	512.0	72329	5.0	.0	2E0	4.80	.10	1.23	.85	16.40		.01	12	30	42	.04		.10			
512.0	517.0	72330	5.0	.0	2E4	4.86	.14	2.25	3.10	24.20		.01	12	30	42	.12		.10			
517.0	522.0	72331	5.0	.0	2E4	4.80	.12	5.19	7.48	47.70		.01	12	30	42	.05		.10			
522.0	527.0	72332	5.0	.0	2E4	4.26	.29	3.08	6.83	30.90		.01	12	30	42	.06		.10			
527.0	532.0	72333	5.0	.0	2E4	4.13	.27	1.57	3.50	20.80		.07	14	22	36	.10		.12			
532.0	537.0	72334	5.0	.0	2F0	4.55	.16	2.05	3.29	20.90		.07	14	22	36	.02		.12			
537.0	542.0	72335	5.0	.0	2HF	4.36	.26	2.49	4.69	20.10		.21	14	22	36	.03		.12			
542.0	547.0	72336	5.0	.0	2D0	3.00	.13	1.18	2.94	18.50		.14	14	22	36	.31		.12			
547.0	552.0	72337	5.0	.0	2A4	2.83	.12	.90	3.26	27.40		.14	5	6	12	.27		.06			
552.0	557.0	72338	5.0	.0	2D0	3.18	.20	1.88	3.35	48.70		.14	5	6	12	.22		.06			
557.0	562.0	72339	5.0	.0	2A4	2.86	.10	1.53	3.74	37.30		.34	5	6	12	.31		.06			
562.0	567.0	72340	5.0	.0	2B4/0	3.67	.05	29.40	2.12	642.20		.14	5	6	12	.20		.06			
567.0	572.0	72341	5.0	.0	2A4	2.86	.14	2.88	4.74	66.70		.07	5	6	12	.24		.06			

DDH: 74-10 UTM-N: 7890.6 UTM-E: 15456.5 UTM-ELEV: 4017.3 TOTAL DEPTH: 508.0 SECTION: 130
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
227.7	230.0	72377	2.3	.0	2CF	3.38	.10	2.33	3.78	34.10		.03	3	8	11	.64		.06			
230.0	234.8	72378	4.8	.0	2B0	2.85	.03	.22	.20	2.70		.03	3	8	11	4.80		.06			
276.0	281.0	72380	5.0	.0	2E3	3.99	.39	.66	.48	19.50			6	18	25	.37		.18			
281.0	286.0	72381	5.0	.0	2GE	4.78	.06	5.43	9.33	62.70		.07	6	18	25	33.59		.18			
286.0	296.0	72382	10.0	.0	2GE	4.52	.26	3.20	6.23	44.80		.14	12	19	32	18.38		.10			
296.0	301.0	72383	5.0	.0	2E4	4.41	.48	4.89	5.51	84.70		.07	12	19	32	.26		.10			
301.0	306.0	72384	5.0	.0	2H4	4.16	.51	4.20	3.73	56.90		.07	12	19	32	1.05		.10			
306.0	311.0	72385	5.0	.0	2E3	3.90	.47	2.20	1.71	40.10		.14	8	29	37	.18		.20			
311.0	316.0	72386	5.0	.0	2E8	4.72	.14	1.14	2.29	19.90		.48	8	29	37	.10		.20			
316.0	321.0	72387	5.0	.0	2E8	3.87	.27	.47	.83	6.50			8	29	37	.11		.20			
321.0	326.0	72388	5.0	.0	2E1	4.52	.34	1.02	.62	20.50			8	29	37	.02		.20			
326.0	331.0	72389	5.0	.0	2E1	4.27	.30	1.53	.48	19.80			7	27	35	.08		.14			
331.0	336.0	72390	5.0	.0	2E4	3.91	.26	1.93	2.70	25.60			7	27	35	.04		.14			
336.0	341.0	72391	5.0	.0	2F0	4.12	.21	3.28	4.98	45.90		.34	7	27	35	.02		.14			
341.0	346.0	72392	5.0	.0	2E4	4.18	.24	1.31	4.76	16.50		.27	7	27	35	.04		.14			
346.0	351.0	72393	5.0	.0	2E4	4.11	.19	3.83	6.20	31.70		.27	5	30	35	.02		.21			
351.0	356.0	72394	5.0	.0	2F1	4.57	.37	1.83	1.19	24.40		.07	5	30	35	.03		.21			
356.0	361.0	72395	5.0	.0	2E4	3.99	.25	1.83	3.19	18.00		.55	5	30	35	.03		.21			
361.0	366.0	72396	5.0	.0	2E8	4.16	.32	3.18	5.54	21.40		.07	5	30	35	.02		.21			
366.0	371.0	72397	5.0	.0	2F0	4.39	.27	3.04	2.75	16.10		.01	4	30	34	.03		.16			
371.0	376.0	72398	5.0	.0	2E4	4.62	.15	4.34	4.55	30.40		.01	4	30	34	.02		.16			
376.0	381.0	72399	5.0	.0	2CE	3.78	.31	1.10	1.50	11.50		.96	4	30	34	.02		.16			
381.0	386.0	72400	5.0	.0	2CE	3.86	.23	1.10	2.17	12.40		.41	4	30	34	.02		.16			
386.0	391.0	72401	5.0	.0	2CE	4.06	.06	3.87	12.75	14.20		.01	3	22	25	.04		.04			
391.0	396.0	72402	5.0	.0	2F4	3.81	.06	4.09	10.43	14.60		.07	3	22	25	.11		.04			
396.0	401.0	72403	5.0	.0	2E4	3.47	.04	2.61	7.54	16.60		.07	3	22	25	.13		.04			
401.0	406.0	72404	5.0	.0	2F0	4.34	.11	3.06	6.24	19.80		.21	3	22	25	.05		.04			
406.0	411.0	72405	5.0	.0	2E4	3.87	.02	2.68	8.45	16.30		.07	3	22	25	.08		.06			
411.0	416.0	72406	5.0	.0	2FE4	4.53	.03	5.25	9.75	28.00		.41	3	22	25	.04		.06			
416.0	421.0	72407	5.0	.0	2E4	4.05	.04	3.42	6.74	19.30		.14	3	22	25	.08		.06			
421.0	426.0	72408	5.0	.0	2C0	2.75	.04	.20	.48	4.90		.07	3	22	25	.35		.06			
426.0	431.0	72409	5.0	.0	2C0	3.04	.05	.23	.43	8.90		.14	5	15	20	.17		.04			
431.0	436.0	72410	5.0	.0	2C0	3.32	.14	1.83	.81	20.90		.07	5	15	20	.12		.04			
436.0	441.0	72411	5.0	.0	2CD	3.51	.06	1.97	5.14	14.30		.14	5	15	20	.12		.04			
441.0	446.0	72412	5.0	.0	2D4	3.18	.25	3.59	10.27	21.10		.14	5	15	20	.10		.04			
446.0	451.0	72413	5.0	.0	2A0	2.75	.15	.50	1.56	9.20			5	6	12	.24		.05			
451.0	456.0	72414	5.0	.0	2A0	3.13	.19	.28	1.88	12.80			5	6	12	.18		.05			

DDH: 74-11 UTM-N: 7682.8 UTM-E: 15538.8 UTM-ELEV: 4017.9 TOTAL DEPTH: 300.0 SECTION: 131
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----						-----ASSAYS-----																	
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.		
159.5	164.7	72419	5.2	.0	****	3.28	.27	.14	.15	6.70		.03	10	11	21	.32		.12					
164.7	167.1	72420	2.4	.0	1D49	2.96	.09	2.33	1.44	56.80		.03	10	11	21	1.30		.12					
167.1	170.5	72421	3.4	.0	2D0	3.45	.06	2.52	4.50	49.20		.03	6	6	13	1.05		.12					
170.5	175.5	72422	5.0	.0	2L0	2.81	.02	.06	.08	1.00		.03	6	6	13	2.47		.12					
175.5	177.6	72423	2.1	.0	2D6	3.62	.07	2.97	1.59	50.00		.03	6	6	13	14.02		.12					
177.6	182.8	72424	5.2	.0	2L0	2.81	.03	.29	.18	4.20		.03	6	6	13	1.82		.12					
182.8	185.0	72425	2.2	.0	2B4	3.52	.05	4.40	4.70	70.80			6	6	13	11.75		.12					
185.0	188.1	72426	3.1	.0	2L0	2.99	.04	.62	.55	10.70			6	6	13	6.12		.12					
188.1	193.0	72427	4.9	.0	2L0	2.97	.03	.33	.10	1.80			5	4	9	3.90		.07					
193.0	196.2	72428	3.2	.0	0Q0	2.88	.01	.18	.08	.10			5	4	9	7.44		.07					
196.2	201.0	72429	4.8	.0	1D0	2.73	.01	.10	.13	.10			5	4	9	4.03		.07					
201.0	206.0	72430	5.0	.0	2DH4	3.32	.12	3.78	7.73	53.30			5	4	9	1.69		.07					
206.0	211.0	72431	5.0	.0	2F4	4.67	.11	7.14	11.90	50.10			3	30	33	.18		.05					
211.0	216.0	72432	5.0	.0	2F4	4.73	.02	3.28	8.71	21.80			3	30	33	.02		.05					
216.0	221.0	72433	5.0	.0	2F4	4.80	.08	3.45	9.17	25.00			3	30	33	.02		.05					
221.0	226.0	72434	5.0	.0	2F4	4.75	.09	6.47	10.90	48.10			3	30	33	.05		.05					
226.0	231.0	72435	5.0	.0	2F4	4.86	.05	5.10	12.06	36.70			3	30	33	.02		.05					
231.0	236.0	72436	5.0	.0	2F4	4.81	.07	3.44	6.68	24.50			2	30	33	.02		.05					
236.0	241.0	72437	5.0	.0	2F4	4.84	.06	3.56	6.65	31.90			2	30	33	.03		.05					
241.0	246.0	72438	5.0	.0	2HF4	4.20	.40	1.90	6.50	36.20			2	30	33	.29		.05					
246.0	251.0	72439	5.0	.0	2HF4	4.37	.29	4.49	8.61	41.60			2	30	33	2.00		.05					
251.0	256.0	72440	5.0	.0	2F0	4.00	.20	2.34	5.31	17.40			16	10	26	.18		.08					
256.0	261.0	72441	5.0	.0	2D0	3.09	.13	1.81	6.43	17.10			16	10	26	.37		.08					
261.0	266.0	72442	5.0	.0	2D0	3.16	.10	4.08	3.76	56.60			16	10	26	.46		.08					
266.0	271.0	72443	5.0	.0	2D0	3.05	.11	1.81	2.64	29.00			16	10	26	.38		.08					
271.0	276.0	72444	5.0	.0	2D0	2.95	.07	2.37	3.09	39.40			4	5	10	.23		.04					
276.0	281.0	72445	5.0	.0	2D0	2.98	.07	4.00	4.45	72.20			4	5	10	.23		.04					
281.0	286.0	72446	5.0	.0	2DA	2.78	.06	1.46	4.18	29.70			4	5	10	.29		.04					
286.0	291.0	72447	5.0	.0	2A0	2.87	.21	.98	.84	52.30			4	5	10	7.19		.04					
291.0	296.0	72448	5.0	.0	2A0	2.64	.05	.76	1.14	9.70			2	2	4	.47		.03					
296.0	300.0	72449	4.0	.0	2B4	2.77	.04	1.16	4.06	15.80			2	2	4	.23		.03					

DDH: 74-15 UTM-N: 9004.0 UTM-E: 14601.9 UTM-ELEV: 4056.9 TOTAL DEPTH: 754.0 SECTION: 120+000
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	---ASSAYS---													
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %
501.0	506.0	72484	5.0	.0	2C09	3.08	.54	.12	.18	10.00			8	20	28	.11		.23		
506.0	511.0	72485	5.0	.0	2C09	3.42	.21	.14	.22	6.60			8	20	28	.07		.23		
511.0	516.0	72486	5.0	.0	2C09	3.60	.13	3.20	4.43	40.70			8	20	28	.15		.23		
516.0	521.0	72487	5.0	.0	2F4	4.34	.19	7.00	8.46	95.90			8	20	28	.92		.23		
521.0	526.0	72488	5.0	.0	2H46	3.98	.24	6.81	10.81	102.40			8	20	28	3.18		.23		
526.0	531.0	72489	5.0	.0	2D6(	3.27	.19	2.51	1.60	39.90			13	14	28	3.28		.31		
531.0	536.0	72490	5.0	.0	2D46	3.97	.22	5.46	7.61	86.70			13	14	28	1.93		.31		
536.0	541.0	72491	5.0	.0	2E43	3.91	.21	5.38	6.50	82.40			13	14	28	3.02		.31		
541.0	546.0	72492	5.0	.0	2E43	3.90	.16	7.56	4.30	134.70			13	14	28	4.46		.31		
546.0	551.0	72493	5.0	.0	2E46	3.99	.17	5.28	5.94	91.60			11	19	30	1.39		.36		
551.0	556.0	72494	5.0	.0	2E4(2	3.36	.26	3.36	2.67	77.20			11	19	30	1.39		.36		
556.0	561.0	72495	5.0	.0	2E49	3.80	.27	3.45	1.70	77.30			11	19	30	.54		.36		
561.0	566.0	72496	5.0	.0	2E8(	3.81	.17	2.00	1.10	70.60			11	19	30	.63		.36		
566.0	571.0	72497	5.0	.0	2E0&	4.46	.20	2.16	1.60	47.70			4	14	19	.31		.18		
571.0	576.0	72498	5.0	.0	2G0(	3.95	.22	3.59	2.80	68.30			4	14	19	3.55		.18		
576.0	581.0	72499	5.0	.0	2B46	3.07	.22	1.29	1.07	43.30			4	14	19	7.48		.18		
581.0	586.0	72500	5.0	.0	2B4(	2.89	.09	2.52	1.24	59.60			4	14	19	6.91		.18		
586.0	591.0	72501	5.0	.0	2E49	4.27	.20	4.53	3.75	64.00			5	31	37	1.27		.20		
591.0	596.0	72502	5.0	.0	2E49	4.34	.32	3.00	4.70	49.60			5	31	37	7.37		.20		
596.0	601.0	72503	5.0	.0	2E9&	4.67	.55	1.02	2.48	12.60			5	31	37	.05		.20		
601.0	606.0	72504	5.0	.0	2F0(	4.70	.25	1.78	4.17	12.00			5	31	37	.02		.20		
606.0	611.0	72505	5.0	.0	2F4(	4.81	.10	3.11	6.26	21.10			3	35	39	.04		.15		
611.0	616.0	72506	5.0	.0	2F4(	4.74	.19	4.95	8.33	32.90			3	35	39	.03		.15		
616.0	621.0	72507	5.0	.0	2E48	4.86	.36	2.73	3.95	20.90			3	35	39	.02		.15		
621.0	626.0	72508	5.0	.0	2F4	4.86	.07	5.35	7.21	32.30			3	35	39	.02		.15		
626.0	631.0	72509	5.0	.0	2E19	4.78	.23	2.45	3.82	23.80			6	34	40	.03		.34		
631.0	636.0	72510	5.0	.0	2E89	4.71	.34	1.18	2.74	18.80			6	34	40	.03		.34		
636.0	641.0	72511	5.0	.0	2E89	4.73	.32	1.92	4.29	19.10			6	34	40	.07		.34		
641.0	646.0	72512	5.0	.0	2E19	4.51	.22	1.72	1.66	18.30			6	34	40	.08		.34		
646.0	651.0	72513	5.0	.0	2E19	4.59	.37	1.64	2.46	16.00			3	35	39	.03		.16		
651.0	656.0	72514	5.0	.0	2F4	4.78	.18	4.63	6.36	28.00			3	35	39	.03		.16		
656.0	661.0	72515	5.0	.0	2F4(	4.69	.19	5.43	5.13	38.80			3	35	39	.03		.16		
661.0	666.0	72516	5.0	.0	2E4(	4.57	.15	2.89	3.91	29.10			3	35	39	.04		.16		
666.0	671.0	72517	5.0	.0	2F0	4.43	.12	2.16	5.30	16.00			6	32	38	.05		.19		
671.0	676.0	72518	5.0	.0	2E43	4.25	.39	2.66	3.93	24.60			6	32	38	.09		.19		
676.0	681.0	72519	5.0	.0	2E18	4.44	.46	.72	2.46	19.20			6	32	38	.03		.19		
681.0	686.0	72520	5.0	.0	2E89	4.31	.39	1.20	2.23	6.80			6	32	38	.11		.19		
686.0	691.0	72521	5.0	.0	2E43	4.28	.31	1.74	2.60	7.80			3	34	37	.20		.08		
691.0	696.0	72522	5.0	.0	2F4(	4.94	.04	3.02	5.25	14.80			3	34	37	.04		.08		
696.0	701.0	72523	5.0	.0	2F4(	4.78	.04	3.14	5.83	16.30			3	34	37	.04		.08		
701.0	706.0	72524	5.0	.0	2F4(	4.90	.09	3.93	7.64	17.00			3	34	37	.02		.08		
706.0	711.0	72525	5.0	.0	2F4(	5.03	.09	3.52	7.77	16.80			6	25	32	.01		.03		
711.0	716.0	72526	5.0	.0	2E43	4.81	.07	3.09	5.22	17.10			6	25	32	.02		.03		
716.0	721.0	72527	5.0	.0	2H9(	4.25	.32	1.74	3.33	14.60			6	25	32	.06		.03		
721.0	726.0	72528	5.0	.0	2A0(	3.04	.13	1.40	2.76	24.10			6	25	32	.29		.03		
726.0	731.0	72529	5.0	.0	2A0	3.03	.21	.08	.22	5.00			7	8	16	.21		.03		
731.0	736.0	72530	5.0	.0	2A0	3.07	.19	.38	.58	7.30			7	8	16	.14		.03		
736.0	741.0	72531	5.0	.0	2D47	3.15	.10	3.44	7.15	33.70			7	8	16	.08		.03		
741.0	743.0	72532	2.0	.0	2C0	3.33	.10	.65	1.06	8.20			7	8	16	.13		.03		

DDH: 74-17 UTM-N: 8431.2 UTM-E: 14404.4 UTM-ELEV: 4031.0 TOTAL DEPTH: 585.0 SECTION: 122+020
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

-----DEPTHS-----						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
484.0	489.0	72541	5.0	.0	2D4	3.43	.08	5.49	15.00	32.90			6	12	19	.81		.20			
489.0	494.0	72542	5.0	.0	2E49	4.55	.20	6.48	7.90	72.50			6	12	19	5.00		.20			
494.0	499.0	72543	5.0	.0	2Q96	3.54	.17	3.63	4.52	51.40			6	12	19	11.75		.20			
499.0	504.0	72544	5.0	.0	2Q96	2.98	.04	.68	.94	10.00			6	12	19	10.06		.20			
504.0	509.0	72545	5.0	.0	2Q&9	3.51	.27	3.91	6.13	55.50			8	20	28	6.12		.32			
509.0	514.0	72546	5.0	.0	2G4(	4.56	.16	5.15	6.52	78.80			8	20	28	17.34		.32			
514.0	519.0	72547	5.0	.0	2G49	4.58	.33	5.76	6.43	89.00			8	20	28	9.84		.32			
519.0	524.0	72548	5.0	.0	2E4(	4.71	.17	6.17	7.05	105.80			8	20	28	1.47		.32			
524.0	529.0	72549	5.0	.0	2E4(	4.30	.08	5.02	6.26	80.30			5	13	18	.13		.18			
529.0	534.0	72550	5.0	.0	2B4(	2.89	.10	2.54	4.87	35.10			5	13	18	.19		.18			
534.0	539.0	72551	5.0	.0	2E41	3.47	.18	3.33	4.70	57.60			5	13	18	.28		.18			
539.0	544.0	72552	5.0	.0	2D0&	2.96	.06	2.85	4.26	79.70			5	13	18	.31		.18			
544.0	549.0	72553	5.0	.0	2D0&	3.00	.15	3.26	3.70	66.80			5	5	10	.54		.12			
549.0	554.0	72554	5.0	.0	2D0&	3.12	.09	4.27	3.77	106.00			5	5	10	.34		.12			
554.0	559.0	72555	5.0	.0	2D0&	3.06	.06	2.00	4.75	53.60			5	5	10	.26		.12			
559.0	564.0	72556	5.0	.0	2D0&	3.10	.06	7.01	4.32	555.00			5	5	10	.33		.12			
564.0	569.0	72557	5.0	.0	0Q9(	2.91	.04	2.91	2.16	62.50			4	5	9	.37		.05			
569.0	574.0	72558	5.0	.0	2D5(	3.00	.15	2.33	3.31	53.40			4	5	9	.36		.05			
574.0	579.0	72559	5.0	.0	2B0(	2.84	.11	1.14	2.10	45.90			4	5	9	.33		.05			
579.0	585.0	72560	6.0	.0	0Q9(	2.84	.04	1.89	.28	27.40			3	2	5	.29		.03			

DDH: 74-18 UTM-N: 7445.1 UTM-E: 15512.9 UTM-ELEV: 4015.5 TOTAL DEPTH: 250.0 SECTION: 132
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
124.0	129.0	72563	5.0	.0	2D0	3.65	.11	2.33	5.85	30.60			.14	11	13	25	.15		.09		
129.0	134.0	72564	5.0	.0	2E4	4.64	.16	3.57	6.39	40.40			.07	11	13	25	.05		.09		
134.0	139.0	72565	5.0	.0	2H4	4.22	.40	3.19	4.65	45.80			.07	11	13	25	.03		.09		
139.0	144.0	72566	5.0	.0	2H4	4.58	.37	5.05	6.82	67.20			.14	11	13	25	.05		.09		
144.0	149.0	72567	5.0	.0	2B0	4.76	.32	1.80	2.98	21.90			.01	10	7	17	.07		.04		
149.0	154.0	72568	5.0	.0	2B4	3.22	.20	.90	4.11	14.40			.07	10	7	17	.57		.04		
154.0	159.0	72569	5.0	.0	2B4	3.03	.11	1.29	2.78	21.60			.01	10	7	17	.45		.04		
159.0	164.0	72570	5.0	.0	2A0	3.06	.14	1.20	2.73	19.40			.21	10	7	17	.78		.04		
164.0	168.0	72571	4.0	.0	2A4	3.11	.03	1.37	6.07	23.30			.27	3	7	11	.48		.03		
168.0	173.0	72572	5.0	.0	2A4	3.05	.02	2.13	1.99	45.60			.62	3	7	11	.45		.03		
173.0	178.0	72573	5.0	.0	2A0	2.99	.05	1.40	2.52	28.80			.34	3	7	11	.42		.03		
178.0	183.0	72574	5.0	.0	2A0	2.68	.02	.66	1.57	12.30				3	7	11	.60		.03		
183.0	188.0	72575	5.0	.0	2A0	2.75	.06	.75	1.49	19.40				3	4	7	.37		.02		
188.0	191.5	72576	3.5	.0	2A0	2.88	.07	.37	.22	11.70				3	4	7	.24		.02		

DDH: 74-19 UTM-N: 7431.3 UTM-E: 15336.4 UTM-ELEV: 4016.4 TOTAL DEPTH: 373.0 SECTION: 131
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
231.0	236.0	72582	5.0	.0	2C0	3.34	.40	.80	.11	15.60				8	8	17	.02				.05
236.0	241.0	72583	5.0	.0	2D0	2.78	.09	1.20	5.32	49.40			.27	8	8	17	.05				.05
241.0	246.0	72584	5.0	.0	2D0	3.39	.14	2.33	3.07	48.00			.07	8	8	17	.33				.05
246.0	251.0	72585	5.0	.0	2D0	3.79	.09	2.83	3.73	37.50			.14	5	10	16	.24				.06
251.0	256.0	72586	5.0	.0	2C0	3.37	.16	1.48	1.92	36.00			.07	5	10	16	.81				.06
256.0	261.0	72587	5.0	.0	2C2	2.98	.08	.80	2.02	21.70			.62	5	10	16	1.03				.06
261.0	266.0	72588	5.0	.0	2D0	2.99	.10	1.58	2.68	38.90			.07	5	10	16	.63				.06
266.0	271.0	72589	5.0	.0	2D0	3.06	.11	2.63	4.93	68.40			.07	4	4	9	.62				.04
271.0	276.0	72590	5.0	.0	2A0	2.96	.10	1.04	2.80	36.80			.34	4	4	9	.47				.04
276.0	281.0	72591	5.0	.0	2A0	2.77	.04	.66	1.22	13.90				4	4	9	.50				.04
281.0	286.0	72592	5.0	.0	2A0	2.98	.11	.60	1.14	19.80				4	4	9	.23				.04
286.0	288.0	72593	2.0	.0	2A0	2.84	.07	.42	.66	13.80				4	4	9	.30				.04

DDH: 74-20 UTM-N: 7690.8 UTM-E: 15281.2 UTM-ELEV: 4004.4 TOTAL DEPTH: 427.0 SECTION: 130
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %
219.0	224.0	72599	5.0	.0	2C0	3.45	.42	.50	.44	10.20			2	24	26	.11		.04		
224.0	229.0	72600	5.0	.0	2C0	3.49	.10	.46	2.95	7.90			.14	2	24	26	.12		.04	
229.0	234.0	72601	5.0	.0	2C0	4.29	.33	.66	2.24	13.30			.01	2	24	26	.12		.04	
234.0	239.0	72602	5.0	.0	2E3	4.94	.02	.28	.74	6.50			.48	3	22	25	.03		.16	
239.0	244.0	72603	5.0	.0	2E4	4.37	.17	5.70	6.79	81.00			.34	3	22	25	.36		.16	
244.0	249.0	72604	5.0	.0	2D6	3.19	.10	2.30	2.56	37.90			.48	3	22	25	2.25		.16	
249.0	254.0	72605	5.0	.0	2D6	3.17	.04	3.39	3.39	67.60			.14	3	22	25	6.07		.16	
254.0	259.0	72606	5.0	.0	2E4	4.17	.23	3.43	4.76	52.30			.21	21	21	43	.31		.14	
259.0	264.0	72607	5.0	.0	2H4	4.50	.40	2.20	3.51	29.60		1.78	21	21	43	.03		.14		
264.0	269.0	72608	5.0	.0	2H4	4.54	.33	3.43	5.24	41.00			.14	21	21	43	.02		.14	
269.0	274.0	72609	5.0	.0	2H4	4.74	.20	2.35	4.14	27.00			.07	21	21	43	.10		.14	
274.0	279.0	72610	5.0	.0	2E4	4.64	.45	3.14	4.90	19.90			.07	6	34	40	.12		.05	
279.0	284.0	72611	5.0	.0	2H4	4.98	.07	3.02	5.44	16.50			.01	6	34	40	.04		.05	
284.0	289.0	72612	5.0	.0	2EF	4.88	.03	3.80	5.24	20.20			.21	6	34	40	.03		.05	
289.0	294.0	72613	5.0	.0	2EF	4.78	.04	2.30	4.00	15.60			.34	6	34	40	.08		.05	
294.0	299.0	72614	5.0	.0	2BC	3.18	.14	1.80	3.49	33.90			.34	6	34	40	.42		.05	

DDH: 74-21 UTM-N: 7191.9 UTM-E: 15402.4 UTM-ELEV: 4014.0 TOTAL DEPTH: 250.0 SECTION: 133
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
99.0	104.0	72619	5.0	.0	2F0	4.37	.18	3.70	3.41	40.50		.34				1.52					
104.0	109.0	72620	5.0	.0	2F4	3.10	.22	6.20	6.14	76.50		.14	7	14	21	1.17		.22			
109.0	114.0	72621	5.0	.0	2F0	3.52	.15	4.08	4.87	55.00		.01	7	14	21	.76		.22			
114.0	119.0	72622	5.0	.0	2D34	3.43	.11	4.10	5.92	59.50		.01	7	14	21	.89		.22			
119.0	124.0	72623	5.0	.0	2C0	3.02	.10	.42	1.08	6.80		.01	7	14	21	3.28		.22			
124.0	127.0	72624	3.0	.0	2E47	4.38	.32	1.56	2.63	24.60			17	22	40	.46		.12			
131.5	135.7	72626	4.2	.0	2C3	2.79	.08	1.17	1.16	25.30			5	4	9	4.85		.03			
135.7	136.3	72627	.6	.0	2H4	4.03	.42	5.46	7.25	83.50			17	22	40	.14		.12			
139.0	144.0	72629	5.0	.0	2B4	4.03	.42	5.46	7.25	83.50			17	22	40	.14		.12			
144.0	149.0	72630	5.0	.0	2A4	3.23	.25	3.70	5.06	58.40			4	4	8	.33		.06			
149.0	154.0	72631	5.0	.0	2A0	2.71	.09	.51	.89	14.60			4	4	8	.74		.06			
154.0	159.0	72632	5.0	.0	2A0	2.56	.06	.26	.34	10.30			4	4	8	.49		.06			
159.0	164.0	72633	5.0	.0	2A0	2.69	.05	2.96	.97	59.90			4	4	8	1.31		.06			
164.0	169.0	72634	5.0	.0	2A0	2.57	.03	.30	.23	13.90			2	1	4	1.38		.01			
169.0	174.0	72635	5.0	.0	2A0	2.66	.06	.34	.75	10.00			2	1	4	.76		.01			
174.0	179.0	72636	5.0	.0	2A0	2.65	.04	.94	1.21	14.20			2	1	4	.74		.01			
179.0	184.0	72637	5.0	.0	2A0	2.57	.03	1.13	1.51	12.60		.07	2	1	4	.68		.01			
184.0	189.0	72638	5.0	.0	2A0	2.65	.09	1.29	2.55	18.30		.34	3	3	7	.24		.05			
189.0	194.5	72639	5.5	.0	2A0	2.78	.15	.92	1.33	15.80			3	3	7	.22		.05			

DDH: 74005 UTM-N: 9606.3 UTM-E: 14193.3 UTM-ELEV: 3902.6 TOTAL DEPTH: 325.0 SECTION:
 RFE: RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----															
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.	
35.0	40.0	72094	5.0	.0	****	3.30	.05	1.86	3.23	41.10			5	7	13	10.22		.08				
40.0	45.0	72095	5.0	.0	****	2.96	.09	.24	.28	10.30			5	7	13	4.17		.08				
45.0	50.0	72096	5.0	.0	****	4.32	.16	3.69	3.53	69.40			10	25	35	1.74		.31				
50.0	55.0	72097	5.0	.0	****	4.67	.13	4.47	4.48	54.30			10	25	35	7.12		.31				
55.0	60.0	72098	5.0	.0	****	4.76	.08	3.60	4.24	37.70			5	33	39	9.55		.25				
60.0	65.0	72099	5.0	.0	****	4.51	.22	4.75	4.06	85.80			5	33	39	2.58		.25				
65.0	70.0	72100	5.0	.0	****	4.42	.19	3.69	4.94	50.50			5	33	39	11.34		.25				
70.0	75.0	72101	5.0	.0	****	4.74	.26	2.79	2.51	35.60			5	33	39	.40		.25				
75.0	80.0	72102	5.0	.0	****	4.41	.24	2.22	2.30	29.30			9	22	31	.28		.27				
80.0	85.0	72103	5.0	.0	****	4.29	.32	7.45	5.88	102.40			9	22	31	12.40		.27				
85.0	90.0	72104	5.0	.0	****	4.44	.23	5.12	5.21	71.60			9	22	31	9.39		.27				
90.0	95.0	72105	5.0	.0	****	4.35	.19	5.38	5.30	76.90			9	22	31	8.10		.27				
95.0	100.0	72106	5.0	.0	****	4.54	.17	3.75	3.53	47.20			5	27	33	.13		.14				
100.0	105.0	72107	5.0	.0	****	3.47	.05	.40	.36	8.00			5	27	33	.04		.14				
105.0	110.0	72108	5.0	.0	****	4.82	.16	6.31	4.15	61.70			5	27	33	.02		.14				
110.0	115.0	72109	5.0	.0	****	4.87	.20	5.92	5.73	59.10			5	27	33	.04		.14				
115.0	120.0	72110	5.0	.0	****	4.71	.19	2.36	1.68	26.70			3	37	41	.02		.08				
120.0	125.0	72111	5.0	.0	****	4.77	.21	1.40	2.67	17.50			3	37	41	.03		.08				
125.0	130.0	72112	5.0	.0	****	4.39	.16	1.18	1.60	10.20			3	37	41	.04		.08				
130.0	135.0	72113	5.0	.0	****	4.10	.54	1.96	1.28	23.00			4	24	28	.12		.14				
135.0	140.0	72114	5.0	.0	****	4.11	.41	.84	.96	13.40			2	36	39	.17		.09				
140.0	145.0	72115	5.0	.0	****	4.58	.06	.50	.46	6.00			2	36	39	.10		.09				
145.0	150.0	72116	5.0	.0	****	4.60	.06	1.14	.16	8.60			2	36	39	.02		.09				
150.0	155.0	72117	5.0	.0	****	5.04	.30	1.44	3.28	10.50			2	36	39	.02		.09				
155.0	160.0	72118	5.0	.0	****	4.61	.34	2.16	3.70	8.10			6	32	39	.03		.20				
160.0	165.0	72119	5.0	.0	****	4.37	.34	1.16	3.49	9.00			6	32	39	.02		.20				
165.0	170.0	72120	5.0	.0	****	4.46	.44	.48	2.53	6.90			6	32	39	.02		.20				
170.0	175.0	72121	5.0	.0	****	4.38	.17	1.46	3.65	7.00			6	32	39	.03		.20				
175.0	180.0	72122	5.0	.0	****	3.79	.23	2.52	4.03	10.30			3	33	36	.17		.05				
180.0	185.0	72123	5.0	.0	****	4.87	.20	3.84	6.14	15.80			3	33	36	.01		.05				
185.0	190.0	72124	5.0	.0	****	4.89	.07	2.52	4.58	9.70			3	33	36	.01		.05				
190.0	195.0	72125	5.0	.0	****	4.88	.05	2.88	8.04	10.30			3	33	36	.01		.05				
195.0	200.0	72126	5.0	.0	****	4.69	.21	2.94	5.64	9.00			5	35	41	.01		.13				
200.0	205.0	72127	5.0	.0	****	4.62	.13	.40	1.86	4.30			5	35	41	.01		.13				
205.0	210.0	72128	5.0	.0	****	4.53	.16	.36	1.18	3.70			5	35	41	.01		.13				
210.0	215.0	72129	5.0	.0	****	4.82	.24	.82	2.03	6.10			5	35	41	.01		.13				
215.0	220.0	72130	5.0	.0	****	4.38	.29	.74	2.07	11.90			7	33	41	.01		.20				
220.0	225.0	72131	5.0	.0	****	4.79	.33	.96	1.60	13.20			7	33	41	.02		.20				
225.0	230.0	72132	5.0	.0	****	4.46	.23	.42	1.34	7.80			7	33	41	.02		.20				
230.0	235.0	72133	5.0	.0	****	4.73	.46	1.64	3.44	13.20			7	33	41	.02		.20				
235.0	240.0	72134	5.0	.0	****	4.47	.38	1.34	3.21	9.60			2	36	39	.01		.05				
240.0	245.0	72135	5.0	.0	****	4.93	.10	3.93	5.27	19.80			2	36	39	.01		.05				
245.0	250.0	72136	5.0	.0	****	4.93	.07	4.00	6.14	15.20			2	36	39	.01		.05				
250.0	255.0	72137	5.0	.0	****	4.86	.18	4.47	7.21	20.40			2	36	39	.02		.05				
255.0	260.0	72138	5.0	.0	****	3.23	.08	3.39	7.41	23.90			3	18	21	.13		.03				
260.0	265.0	72139	5.0	.0	****	3.46	.04	2.79	4.79	22.70			3	18	21	.11		.03				
265.0	270.0	72140	5.0	.0	****	3.58	.08	4.99	10.81	32.90			3	18	21	.07		.03				
270.0	275.0	72141	5.0	.0	****	4.40	.04	3.33	8.09	22.00			3	18	21	.02		.03				
275.0	280.0	72142	5.0	.0	****	4.95	.02	3.60	7.07	17.60			3	27	30	.01		.04				
280.0	285.0	72143	5.0	.0	****	5.13	.04	3.48	5.36	16.80			3	27	30	.01		.04				
285.0	290.0	72144	5.0	.0	****	3.73	.06	4.31	11.03	19.70			3	27	30	.06		.04				

DDH: 74005 UTM-N: 9606.3 UTM-E: 14193.3 UTM-ELEV: 3902.6 TOTAL DEPTH: 325.0 SECTION:
 RFE: RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
290.0	295.0	72145	5.0	.0	****	3.45	.06	4.99	9.57	23.00				3	27	30	.09		.04		
295.0	300.0	72146	5.0	.0	****	3.49	.06	4.78	12.90	33.50				3	15	19	.09		.04		
300.0	305.0	72147	5.0	.0	****	3.24	.05	2.43	7.24	25.00				3	15	19	.09		.04		
305.0	310.0	72148	5.0	.0	****	3.25	.06	1.36	.88	18.80				3	15	19	.06		.04		
310.0	315.0	72149	5.0	.0	****	3.29	.06	.28	1.24	7.70				3	15	19	.10		.04		
315.0	320.0	72150	5.0	.0	****	3.22	.29	.18	1.52	12.20				6	7	13	.20		.06		
320.0	325.0	72151	5.0	.0	****	2.80	.08	1.58	2.16	29.50				6	7	13	.21		.06		

DDH: 74006 UTM-N: 9815.2 UTM-E: 14343.8 UTM-ELEV: 3979.8 TOTAL DEPTH: 407.0 SECTION:
 RFE: RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	---ASSAYS---													
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %
27.0	32.0	72154	5.0	.0	****	3.68	.06	3.56	7.09	59.00			5	25	31	.29		.27		
32.0	37.0	72155	5.0	.0	****	4.43	.02	4.14	7.74	52.10			5	25	31	7.68		.27		
37.0	42.0	72156	5.0	.0	****	4.58	.09	6.98	5.73	95.50			5	25	31	26.98		.27		
42.0	47.0	72157	5.0	.0	****	4.48	.13	5.56	4.83	86.80			5	25	31	12.50		.27		
47.0	52.0	72158	5.0	.0	****	4.70	.03	2.55	2.89	46.40			5	25	31	1.36		.27		
52.0	57.0	72159	5.0	.0	****	4.68	.10	5.83	5.60	88.90			4	9	14	19.37		.17		
57.0	62.0	72160	5.0	.0	****	4.64	.08	7.81	7.17	103.30			4	9	14	31.49		.17		
62.0	67.0	72161	5.0	.0	****	3.45	.09	3.20	3.10	54.00			4	9	14	7.37		.17		
67.0	72.0	72162	5.0	.0	****	2.76	.02		.22	3.50			4	9	14	.37		.17		
72.0	77.0	72163	5.0	.0	****	2.72	.03	.01		3.90			3	9	12	.52		.05		
77.0	82.0	72164	5.0	.0	****	2.86	.11	.27	.27	10.40			3	9	12	.59		.05		
82.0	87.0	72165	5.0	.0	****	3.55	.06	2.27	5.33	50.00			3	9	12	.16		.05		
87.0	92.0	72166	5.0	.0	****	3.14	.07	.90	4.59	30.20			3	9	12	.27		.05		
92.0	97.0	72167	5.0	.0	****	2.80	.05	.53	.61	22.20			8	13	22	.74		.05		
97.0	102.0	72168	5.0	.0	****	3.75	.49	1.80	1.26	46.40			8	13	22	.30		.05		
102.0	107.0	72169	5.0	.0	****	4.20	.10	3.37	8.78	35.20			8	13	22	.95		.05		
107.0	112.0	72170	5.0	.0	****	3.32	.07	3.44	4.20	50.20			8	13	22	.23		.05		
112.0	117.0	72171	5.0	.0	****	4.06	.14	2.71	5.79	37.40			2	32	34	.10		.04		
117.0	122.0	72172	5.0	.0	****	4.64	.15	3.04	4.13	31.00			2	32	34	.06		.04		
122.0	127.0	72173	5.0	.0	****	4.66	.36	3.67	4.41	41.80			2	32	34	.05		.04		
127.0	132.0	72174	5.0	.0	****	4.13	.16	2.91	3.71	23.80			2	32	34	.07		.04		
132.0	137.0	72175	5.0	.0	****	4.67	.31	.62	.72	11.90			6	31	38	.04		.20		
137.0	142.0	72176	5.0	.0	****	4.60	.50	1.74	1.79	23.50			6	31	38	.04		.20		
142.0	147.0	72177	5.0	.0	****	4.76	.14	5.31	6.86	26.40			6	31	38	.02		.20		
147.0	152.0	72178	5.0	.0	****	4.36	.14	1.88	3.87	20.80			6	31	38	.03		.20		
152.0	157.0	72179	5.0	.0	****	4.15	.11	1.30	3.03	9.10			5	29	35	.02		.11		
157.0	162.0	72180	5.0	.0	****	3.95	.33		1.47	7.80			5	29	35	.03		.11		
162.0	167.0	72181	5.0	.0	****	4.25	.32		1.22	7.50			5	29	35	.02		.11		
167.0	172.0	72182	5.0	.0	****	4.19	.21		.98	4.70			5	29	35	.02		.11		
172.0	177.0	72183	5.0	.0	****	4.51	.47	.26	1.11	6.40			6	32	38	.04		.12		
177.0	182.0	72184	5.0	.0	****	4.34	.58	.17	.50	12.40			6	32	38	.04		.12		
182.0	187.0	72185	5.0	.0	****	4.60	.16	.22	1.40	2.80			6	32	38	.02		.12		
187.0	192.0	72186	5.0	.0	****	4.27	.07	3.15	6.41	7.80			6	32	38	.02		.12		
192.0	197.0	72187	5.0	.0	****	4.09	.05	5.38	13.38	15.60			3	20	23	.05		.04		
197.0	202.0	72188	5.0	.0	****	4.07	.06	7.53	15.30	23.90			3	20	23	.08		.04		
202.0	207.0	72189	5.0	.0	****	4.02	.04	3.89	9.17	15.00			3	20	23	.04		.04		
207.0	212.0	72190	5.0	.0	****	3.83	.04	3.70	10.71	13.70			3	20	23	.07		.04		
212.0	217.0	72191	5.0	.0	****	4.34	.04	5.76	12.69	21.70			2	26	28	.03		.04		
217.0	222.0	72192	5.0	.0	****	4.47	.03	4.92	9.88	22.90			2	26	28	.03		.04		
222.0	227.0	72193	5.0	.0	****	4.07	.04	2.49	7.07	19.00			2	26	28	.11		.04		
227.0	232.0	72194	5.0	.0	****	4.11	.02	1.66	6.88	12.10			2	26	28	.07		.04		
232.0	237.0	72195	5.0	.0	****	3.71	.04	2.93	7.69	18.30			3	12	16	.12		.04		
237.0	242.0	72196	5.0	.0	****	3.27	.05	1.50	7.66	9.20			3	12	16	.13		.04		
242.0	247.0	72197	5.0	.0	****	3.03	.07	1.37	4.71	14.80			3	12	16	.18		.04		
247.0	252.0	72198	5.0	.0	****	3.19	.05	1.34	3.84	12.60			3	12	16	.12		.04		
252.0	257.0	72199	5.0	.0	****	3.18	.04	.95	5.01	10.30			2	24	27	.18		.04		
257.0	262.0	72200	5.0	.0	****	3.12	.04	.23	1.05	6.60			2	24	27	.24		.04		
262.0	267.0	72201	5.0	.0	****	4.00	.06	.21	4.96	11.20			2	24	27	.04		.04		
267.0	272.0	72202	5.0	.0	****	4.91	.01	1.01	2.99	8.30			2	24	27	.01		.04		
272.0	277.0	72203	5.0	.0	****	4.18	.07	4.40	10.92	26.70			4	19	23	.01		.03		
277.0	282.0	72204	5.0	.0	****	4.18	.04	8.13	18.20	34.50			2	26	28	.02		.02		

DDH: 74006 UTM-N: 9815.2 UTM-E: 14343.8 UTM-ELEV: 3979.8 TOTAL DEPTH: 407.0 SECTION:
 RFE: RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS----		-----ASSAYS-----																			
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
282.0	287.0	72205	5.0	.0	****	4.66	.03	7.73	16.30	33.70			2	26	28	.02		.02			
287.0	292.0	72206	5.0	.0	****	4.83	.02	8.08	12.83	36.10			2	26	28	.02		.02			
292.0	297.0	72207	5.0	.0	****	4.50	.03	8.96	15.00	38.30			2	20	22	.06		.02			
297.0	302.0	72208	5.0	.0	****	3.65	.07	7.47	18.60	35.00			2	20	22	.07		.02			
302.0	307.0	72209	5.0	.0	****	4.42	.05	5.06	8.55	26.40			3	25	28	.02		.02			
307.0	312.0	72210	5.0	.0	****	3.95	.07	7.17	16.90	31.90			4	12	17	.03		.02			
312.0	317.0	72211	5.0	.0	****	4.07	.11	6.33	15.60	28.80			4	16	20	.02		.03			
317.0	322.0	72212	5.0	.0	****	4.88	.03	5.36	7.45	24.30			1	35	37	.01		.01			
322.0	327.0	72213	5.0	.0	****	4.76	.07	3.03	5.66	15.10			1	35	37	.01		.01			
327.0	332.0	72214	5.0	.0	****	4.13	.06	2.52	7.00	17.30			1	35	37	.04		.01			
332.0	337.0	72215	5.0	.0	****	3.21	.06	.82	1.88	9.70			3	26	29	.17		.04			
337.0	342.0	72216	5.0	.0	****	3.54	.06	2.28	4.78	18.10			3	26	29	.04		.04			
342.0	347.0	72217	5.0	.0	****	3.95	.07	.95	2.71	12.80			3	26	29	.03		.04			
347.0	352.0	72218	5.0	.0	****	4.73	.03	2.40	3.95	19.60			3	26	29	.01		.04			
352.0	357.0	72219	5.0	.0	****	4.51	.03	1.72	4.78	16.30			4	30	34	.02		.06			
357.0	362.0	72220	5.0	.0	****	4.34	.08	1.15	3.72	19.20			4	30	34	.06		.06			
362.0	367.0	72221	5.0	.0	****	3.86	.07	.65	3.02	9.40			4	30	34	.05		.06			
367.0	372.0	72222	5.0	.0	****	3.83	.06	2.35	4.38	21.60			4	30	34	.05		.06			
372.0	377.0	72223	5.0	.0	****	3.33	.10	1.73	4.22	16.70			4	18	22	.19		.02			
377.0	382.0	72224	5.0	.0	****	4.03	.05	4.53	11.75	29.00			4	20	24	.08		.02			
382.0	387.0	72225	5.0	.0	****	4.20	.03	3.90	10.00	25.40			4	22	26	.03		.02			
387.0	392.0	72226	5.0	.0	****	3.53	.05	2.31	9.82	19.00			4	18	22	.06		.02			
392.0	397.0	72227	5.0	.0	****	3.09	.05	1.20	3.98	14.00			6	12	18	.13		.07			
397.0	402.0	72228	5.0	.0	****	3.52	.09	3.33	8.79	25.30			6	12	18	.13		.07			
402.0	407.0	72229	5.0	.0	****	3.31	.23	4.82	5.16	56.40			6	12	18	.15		.07			

DDH: 74009 UTM-N: 9404.4 UTM-E: 13993.3 UTM-ELEV: 3923.4 TOTAL DEPTH: 311.0 SECTION:
 RFE: RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %
171.0	176.0	72345	5.0	.0	****	3.30	.10	1.55	5.01	23.70			7	21	29	.17		.21		
176.0	181.0	72346	5.0	.0	****	3.91	.21	2.06	4.83	29.10			7	21	29	.09		.21		
181.0	186.0	72347	5.0	.0	****	4.40	.22	5.99	8.01	74.60			7	21	29	.11		.21		
186.0	191.0	72348	5.0	.0	****	4.63	.22	6.37	7.04	83.60			7	21	29	.60		.21		
191.0	196.0	72349	5.0	.0	****	4.36	.13	2.98	3.92	43.00			7	21	29	.38		.21		
196.0	201.0	72350	5.0	.0	****	4.25	.26	5.60	6.78	74.50			6	35	42	.22		.26		
201.0	206.0	72351	5.0	.0	****	4.59	.13	4.19	4.99	57.70			6	35	42	.25		.26		
206.0	211.0	72352	5.0	.0	****	4.54	.18	5.98	5.83	82.30			6	35	42	4.51		.26		
211.0	216.0	72353	5.0	.0	****	4.41	.32	4.79	4.59	75.60			6	35	42	.30		.26		
216.0	221.0	72354	5.0	.0	****	4.61	.24	7.75	8.10	93.90			7	23	30	.10		.50		
221.0	226.0	72355	5.0	.0	****	5.02	.18	7.42	7.36	102.50			2	18	21	10.21		.09		
226.0	231.0	72356	5.0	.0	****	4.75	.11	7.64	9.46	89.00			2	18	21	26.78		.09		
231.0	236.0	72357	5.0	.0	****	4.68	.07	6.97	8.46	72.40			2	18	21	29.28		.09		
236.0	241.0	72358	5.0	.0	****	4.65	.13	3.56	4.65	37.90			3	20	23	11.23		.16		
241.0	246.0	72359	5.0	.0	****	4.75	.24	8.43	8.13	100.70			3	20	23	11.30		.16		
246.0	251.0	72360	5.0	.0	****	4.55	.18	10.10	8.67	123.20			3	20	23	14.82		.16		
251.0	256.0	72361	5.0	.0	****	4.76	.11	7.14	8.17	73.50			3	20	23	32.13		.16		
256.0	261.0	72362	5.0	.0	****	4.86	.37	2.20	1.82	26.10			4	34	38	.76		.03		
261.0	266.0	72363	5.0	.0	****	5.35	.19	3.25	4.34	22.20			4	34	38	.05		.03		
266.0	271.0	72364	5.0	.0	****	4.70	.13	5.59	7.59	41.60			4	34	38	.06		.03		
271.0	276.0	72365	5.0	.0	****	4.68	.51	3.42	6.81	40.60			4	34	38	.09		.03		
276.0	281.0	72366	5.0	.0	****	4.45	.68	3.00	5.58	34.80			11	3	15	.07		.04		
281.0	286.0	72367	5.0	.0	****	2.87	.18	2.10	4.39	28.80			11	3	15	.27		.04		
286.0	291.0	72368	5.0	.0	****	2.72	.10	1.18	1.38	9.30			11	3	15	.23		.04		
291.0	296.0	72369	5.0	.0	****	2.69	.05	1.38	2.26	8.60			11	3	15	.24		.04		
296.0	301.0	72370	5.0	.0	****	2.76	.14	1.30	1.88	13.70			4	2	6	.21		.04		
301.0	306.0	72371	5.0	.0	****	2.67	.12	2.10	2.67	21.60			4	2	6	.26		.04		
306.0	311.0	72372	5.0	.0	****	2.78	.13	1.92	2.19	30.60			4	2	6	.29		.04		

PAGE: 92

[illegible]

DDH: 75-03 UTM-N: 9214.5 UTM-E: 14972.6 UTM-ELEV: 4139.6 TOTAL DEPTH: 688.0 SECTION: 121+000
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

-----DEPTHS-----						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
529.0	535.0	72715	6.0	.0	2D9&	4.00	.39	3.01	5.26	35.70			3	18	21	.11		.07			
535.0	540.0	72716	5.0	.0	2D4&	3.42	.10	3.30	7.80	3.40			3	18	21	.18		.07			
540.0	545.0	72717	5.0	.0	2E10	3.76	.07	1.91	4.41	18.50			3	18	21	.10		.07			
545.0	550.0	72718	5.0	.0	2C8&	3.48	.17	1.83	3.90	18.50			3	18	21	.10		.07			
550.0	555.0	72719	5.0	.0	2C8&	3.94	.24	.21	.77	10.30			3	24	27	.05		.13			
555.0	560.0	72720	5.0	.0	2C89	3.51	.20	.22	1.08	3.40			3	24	27	.15		.13			
560.0	565.0	72721	5.0	.0	2C39	4.07	.39	.09	1.06	2.70			3	24	27	.06		.13			
565.0	570.0	72722	5.0	.0	2C9&	3.60	.24	.60	2.22	8.20			3	24	27	.09		.13			
570.0	575.0	72723	5.0	.0	2C0&	3.58	.11	.20	.40	10.30			1	21	23	.09		.02			
575.0	580.0	72724	5.0	.0	2C50	3.51	.19	.06	.14	1.40			1	21	23	.10		.02			
580.0	585.0	72725	5.0	.0	2C5	3.58	.18	.29	.90				1	21	23	.11		.02			
585.0	590.0	72726	5.0	.0	2C39	3.91	.21	.48	.70	4.50			1	21	23	.08		.02			
590.0	595.0	72727	5.0	.0	2C39	3.89	.42	.35	.86	3.40			3	16	20	.06		.04			
595.0	600.0	72728	5.0	.0	2D0&	3.64	.06	2.30	6.36	7.50			3	16	20	.09		.04			
600.0	605.0	72729	5.0	.0	2D4&	3.42	.13	3.20	7.58	32.20			3	16	20	.13		.04			
605.0	610.0	72730	5.0	.0	2C0&	2.87	.14	1.40	1.90	17.80			3	16	20	.31		.04			
610.0	615.0	72731	5.0	.0	2L00	2.92	.15	.55	1.31	6.90			3	4	7	.20		.04			
615.0	620.0	72732	5.0	.0	2L0	2.83	.09	.27	.95	8.90			3	4	7	.12		.04			
620.0	625.0	72733	5.0	.0	2L0	2.67	.02	.03	.17	6.20			3	4	7	.15		.04			
625.0	630.0	72734	5.0	.0	2A00	2.82	.04	.86	1.15	15.80			3	4	7	.16		.04			
630.0	635.0	72735	5.0	.0	2A4	2.75	.09	1.65	3.90	32.90			3	4	7	.32		.03			
635.0	640.0	72736	5.0	.0	2A4	2.88	.12	.84	3.60	19.50			3	4	7	.41		.03			
640.0	645.0	72737	5.0	.0	2A4	2.89	.06	1.10	3.60	22.30			3	4	7	.32		.03			
645.0	650.0	72738	5.0	.0	2A0	2.89	.13	1.27	2.20	25.70			3	4	7	.27		.03			
650.0	655.0	72739	5.0	.0	2C00	2.87	.11	.72	1.63	25.00			2	3	6	.24		.02			
655.0	660.0	72740	5.0	.0	2C00	2.86	.09	.70	1.32	20.60			2	3	6	.20		.02			
660.0	665.0	72741	5.0	.0	2A4	2.75	.10	1.60	3.62	34.00			2	1	4	.22		.01			
665.0	670.0	72742	5.0	.0	2A4	2.84	.06	1.06	3.19	16.40			2	1	4	.18		.01			
670.0	675.8	72743	5.8	.0	2A40	2.83	.12	2.38	4.93	41.90			3	2	5	.16		.04			
675.8	677.9	72744	2.1	.0	2D9&	2.95	.27	1.57	4.11	25.80			3	2	5	.12		.04			

DDH: 75-04 UTM-N: 7802.5 UTM-E: 15601.2 UTM-ELEV: 4018.4 TOTAL DEPTH: 482.0 SECTION: 131
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %
210.5	218.0	72747	7.5	.0	****	3.17	.07	.30	.53	6.80			9	14	23	.10		.12		
218.0	223.0	72748	5.0	.0	2E74	4.25	.26	3.85	5.72	74.70			9	14	23	.11		.12		
223.0	228.0	72749	5.0	.0	2E74	4.06	.21	5.78	9.95	85.70			9	14	23	.16		.12		
228.0	233.0	72750	5.0	.0	2EH4	4.21	.28	4.55	7.30	58.30			14	22	37	.17		.09		
233.0	237.5	72751	4.5	.0	2EH4	4.32	.31	3.40	4.95	56.00			14	22	37	.15		.09		
283.0	288.0	72753	5.0	.0	2B4	3.60	.19	8.82	.52	148.10			6	16	23	.20		.26		
288.0	293.0	72754	5.0	.0	2E4	4.16	.22	2.70	3.71	26.10			5	31	37	.11		.39		
293.0	298.0	72755	5.0	.0	2E4	3.85	.34	3.60	4.02	38.40			5	31	37	.16		.39		
298.0	303.0	72756	5.0	.0	2E4	4.34	.36	2.55	1.68	28.00			5	31	37	.13		.39		
303.0	308.0	72757	5.0	.0	2E0	4.67	.39	.70	.56				5	31	37	.15		.39		
308.0	313.0	72758	5.0	.0	2E4	4.46	.33	2.18	2.14	17.80			4	34	39	.14		.24		
313.0	318.0	72759	5.0	.0	2E4	4.67	.16	2.40	2.70	26.10			4	34	39	.13		.24		
318.0	323.0	72760	5.0	.0	2E4	4.52	.41	3.30	2.76	40.50			4	34	39	.14		.24		
323.0	328.0	72761	5.0	.0	2E4	4.63	.33	2.23	2.73	21.90			4	34	39	.13		.24		
328.0	333.0	72762	5.0	.0	2E4	3.97	.13	2.96	5.70	33.60			1	28	30	.14		.05		
333.0	338.0	72763	5.0	.0	2E0	3.76	.24	1.07	1.98	22.60			1	28	30	.14		.05		
338.0	343.0	72764	5.0	.0	2E0	4.06	.27	1.41	1.62	19.90			1	28	30	.21		.05		
343.0	348.0	72765	5.0	.0	2E0	4.04	.30	1.30	2.10	6.20			1	28	30	.15		.05		
348.0	353.0	72766	5.0	.0	2E0	3.82	.30	1.00	1.16	2.10			1	28	30	.14		.02		
353.0	358.0	72767	5.0	.0	2E4	3.59	.34	1.53	2.66	15.10			1	28	30	.14		.02		
358.0	363.0	72768	5.0	.0	2E0	3.96	.24	1.13	2.07	5.40			1	28	30	.15		.02		
363.0	368.0	72769	5.0	.0	2E4	4.10	.13	3.47	5.63	20.60			1	28	30	.15		.02		
368.0	373.0	72770	5.0	.0	2E0	4.24	.42	1.26	1.78	3.40			3	30	34	.13		.17		
373.0	378.0	72771	5.0	.0	2E0	4.15	.26	1.07	1.13	3.40			3	30	34	.14		.17		
378.0	383.0	72772	5.0	.0	2E0	4.27	.38	1.95	1.91	8.60			3	30	34	.13		.17		
383.0	388.0	72773	5.0	.0	2E4	4.25	.26	2.33	3.15	21.20			3	30	34	.12		.17		
388.0	393.0	72774	5.0	.0	2E1	3.89	.22	1.05	2.35	8.90			3	24	27	.14		.16		
393.0	398.0	72775	5.0	.0	2E4	3.96	.25	1.75	5.19	6.20			3	24	27	.17		.16		
398.0	403.0	72776	5.0	.0	2E4	3.83	.18	1.03	3.74	3.40			3	24	27	.15		.16		
403.0	408.0	72777	5.0	.0	2E1	4.07	.37	.37	2.63				3	24	27	.14		.16		
408.0	413.0	72778	5.0	.0	2F4	4.21	.14	3.78	8.50	17.10			3	21	25	.14		.05		
413.0	418.0	72779	5.0	.0	2D4	3.42	.09	3.28	8.35	20.60			3	21	25	.08		.05		
418.0	423.0	72780	5.0	.0	2F4	4.13	.06	4.80	11.30	19.90			3	21	25	.06		.05		
423.0	426.2	72781	3.2	.0	2D4	3.57	.13	4.45	6.76	21.90			3	21	25	.24		.05		

DDH: 75-05 UTM-N: 9495.1 UTM-E: 14907.1 UTM-ELEV: 4109.7 TOTAL DEPTH: 651.0 SECTION: 119+000
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

							-----ASSAYS-----														
-----DEPTHS-----	SAMPLE	INT.	REC.	ROCK	S.G.		Cu	Pb	Zn	Ag(AA)	Ag(FA)	Au(FA)	Po	Py	TOT	BaO	Hg	Mn	As	Ba	S.G.
FROM TO NO.	NO.			UNIT	PULP		%	%	%	g/mT	g/mT	g/mT	%	%	Fe	%	%	%	%	%	W.R.
294.5 308.3	72785	13.8	.0	2D49	3.51		.20	3.90	8.43	54.20				7 11	19	.87		.12			
327.0 333.5	72787	6.5	.0	2D0	3.39		.23	2.44	5.51	41.80				7 10	17	.13		.05			
380.0 385.0	72789	5.0	.0	0Q9	3.11		.07	15.00	.32	246.90				4 9	14	.32		.04			
385.0 390.0	72790	5.0	.0	0Q9	3.34		.16	11.00	1.84	176.90				4 9	14	.28		.04			
390.0 395.0	72791	5.0	.0	2E14	3.26		.20	1.62	3.83	28.80				4 9	14	.21		.04			
395.0 400.0	72792	5.0	.0	2C35	3.50		.23	1.60	2.45	32.20				4 9	14	.18		.04			
400.0 405.0	72793	5.0	.0	2E19	3.48		.35	2.20	4.48	12.30				2 20	22	.17		.03			
405.0 410.0	72794	5.0	.0	2C39	3.55		.38	1.58	1.92	24.70				2 20	22	.19		.03			
410.0 415.0	72795	5.0	.0	2C35	3.31		.11	2.37	1.35	40.40				2 20	22	.19		.03			
415.0 420.0	72796	5.0	.0	2E19	3.95		.20	.38	1.16	12.30				2 20	22	.15		.03			
420.0 425.0	72797	5.0	.0	2E19	4.13		.34	.50	1.32	10.30				1 29	30	.16		.03			
425.0 430.0	72798	5.0	.0	2E19	4.02		.31	.34	.83	10.30				1 29	30	.15		.03			
430.0 435.0	72799	5.0	.0	2E19	3.88		.43	.06	.34	11.60				1 29	30	.16		.03			
435.0 440.0	72800	5.0	.0	2E19	4.05		.22	1.58	2.60	16.40				1 29	30	.18		.03			
440.0 445.0	72801	5.0	.0	2Q0	3.45		.48	1.10	1.17	27.40				5 10	15	.14		.06			
445.0 450.0	72802	5.0	.0	1D4	3.07		.34	1.57	.15	59.70				5 10	15	.20		.06			
450.0 455.0	72803	5.0	.0	1D4	3.19		.07	1.05	2.35	16.40				5 10	15	.21		.06			
455.0 460.0	72804	5.0	.0	1D4	3.33		.11	2.28	1.41	19.90				5 10	15	.20		.06			
460.0 465.0	72805	5.0	.0	2A43	3.52		.05	2.10	4.64	12.30				1 20	21	.20		.01			
465.0 470.0	72806	5.0	.0	2E41	4.05		.07	2.20	2.93	23.30				1 20	21	.19		.01			
470.0 475.0	72807	5.0	.0	2A43	3.62		.07	2.85	4.11	10.30				1 20	21	.18		.01			
475.0 480.0	72808	5.0	.0	2A43	3.61		.06	1.07	3.80	4.80				1 20	21	.20		.01			
480.0 485.0	72809	5.0	.0	2A43	3.50		.06	2.88	6.52	18.50				1 18	19	.20					
485.0 490.0	72810	5.0	.0	2A43	3.15		.06	2.14	7.25	6.90				1 18	19	.20					
490.0 495.0	72811	5.0	.0	2A43	3.28		.09	.97	4.95	8.90				1 18	19	.19					
495.0 500.0	72812	5.0	.0	2E15	3.45		.07	1.10	2.81					1 18	19	.20					
500.0 505.0	72813	5.0	.0	2A43	3.25		.08	2.28	5.22	11.60				1 16	17	.20					
505.0 510.0	72814	5.0	.0	2A43	3.12		.04	2.12	5.90	11.00				1 16	17	.23					
510.0 515.0	72815	5.0	.0	2A43	3.21		.11	3.00	6.88	16.40				1 16	17	.22					
515.0 520.0	72816	5.0	.0	2A43	3.22		.06	1.50	5.60					1 16	17	.21					
520.0 525.0	72817	5.0	.0	2A43	3.10		.05	1.65	4.20					1 16	17	.10		.02			
525.0 530.0	72818	5.0	.0	2A43	4.27		.10	1.76	6.32	11.00				1 16	17	.19		.02			
530.0 535.0	72819	5.0	.0	2A43	3.76		.05	3.62	4.82	8.20				1 16	17	.11		.02			
535.0 540.0	72820	5.0	.0	2A3	3.36		.05	.64	1.92	8.20				1 16	17	.13		.02			
540.0 545.0	72821	5.0	.0	2A3	3.82		.07	.81	1.61	14.40				1 16	17	.13		.02			
545.0 550.0	72822	5.0	.0	2A3	3.72		.05	.75	1.69	9.60				1 16	17	.17		.02			
550.0 555.0	72823	5.0	.0	2A3	3.65		.04	1.35	3.71	11.00				1 16	17	.12		.02			
555.0 560.0	72824	5.0	.0	2A3	3.64		.05	.65	1.47					1 16	17	.13		.02			
560.0 565.0	72825	5.0	.0	2A3	3.17		.03	.75	1.26	13.00				1 16	17	.16		.02			
565.0 570.0	72826	5.0	.0	2A3	3.70		.05	.45	1.66					1 16	17	.13		.02			
570.0 575.0	72827	5.0	.0	2D4&	3.97		.08	2.82	11.40	19.20				1 16	17	.19		.02			
575.0 580.0	72828	5.0	.0	2C35	3.34		.15	.29	.99					1 16	17	.13		.02			
580.0 585.0	72829	5.0	.0	2A13	3.26		.03	.50	1.10	10.30				1 15	17	.18		.02			
585.0 590.0	72830	5.0	.0	2E0	3.66		.03	1.72	4.98	20.60				1 15	17	.19		.02			
590.0 595.0	72831	5.0	.0	2D4	3.80		.04	6.24	17.30	30.90				1 15	17	.17		.02			
595.0 600.0	72832	5.0	.0	2D4	4.20		.03	4.31	11.60	37.70				1 15	17	.18		.02			
600.0 605.0	72833	5.0	.0	2E4	4.78		.02	2.95	7.25	20.60				3 16	19	.15		.05			
605.0 610.0	72834	5.0	.0	2E4	3.83		.07	2.60	4.12	43.20				3 16	19	.17		.05			
610.0 615.0	72835	5.0	.0	2D4	3.19		.12	3.58	6.80	35.70				3 16	19	.19		.05			

DDH: 75-05 UTM-N: 9495.1 UTM-E: 14907.1 UTM-ELEV: 4109.7 TOTAL DEPTH: 651.0 SECTION: 119+000
RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

-----DEPTHS-----				-----ASSAYS-----																
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
615.0	617.0	72836	2.0	.0	2D0	3.03	.08	4.07	8.45	43.20				3 16 19	.18		.05			

DDH: 75-09 UTM-N: 9365.1 UTM-E: 14773.7 UTM-ELEV: 4063.7 TOTAL DEPTH: 723.0 SECTION: 119+000
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

-----DEPTHS-----						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
327.0	329.0	72918	2.0	.0	2E4	4.50	.11	4.09	4.92	49.39				3 19	22	7.74		.31			
329.0	334.0	72919	5.0	.0	2G4	4.67	.19	8.25	6.86	108.40				3 19	22	31.49		.31			
334.0	339.0	72920	5.0	.0	2E2	4.63	.11	4.73	4.48	71.29				1 27	29	13.83		.07			
339.0	344.0	72921	5.0	.0	2G42	4.78	.05	3.31	5.87	46.60				1 27	29	7.20		.07			
344.0	349.0	72922	5.0	.0	2G42	4.80	.02	3.97	8.47	48.70				1 27	29	24.25		.07			
349.0	354.0	72923	5.0	.0	2G42	4.84	.11	2.91	6.00	47.29				1 27	29	8.15		.07			
354.0	359.0	72924	5.0	.0	2D0	3.64	.23	4.49	8.42	69.90				6 6	13	1.85		.05			
359.0	364.0	72925	5.0	.0	1D4	3.06	.08	2.50	5.91	50.10				6 6	13	.17		.05			
364.0	369.0	72926	5.0	.0	1D4	2.75	.07	.10	.29					6 6	13	.19		.05			
369.0	374.0	72927	5.0	.0	2D4&	3.29	.05	1.62	5.83	14.40				6 6	13	.08		.05			
374.0	379.0	72928	5.0	.0	2D4&	3.66	.07	2.04	6.04	29.49					30 31	.08		.02			
379.0	384.0	72929	5.0	.0	2E1	4.15	.28	2.02	3.52	21.19					30 31	.08		.02			
384.0	389.0	72930	5.0	.0	2E19	4.06	.24	.27	.72	8.19					30 31	.05		.02			
389.0	394.0	72931	5.0	.0	2E19	4.02	.40	.28	.39	18.50					30 31	.05		.02			
394.0	399.0	72932	5.0	.0	2C39	3.60	.17	.69	1.55	20.60				3 27	31	.07		.17			
399.0	404.0	72933	5.0	.0	2E1&	4.13	.11	.46	.63	1.39				3 27	31	.04		.17			
404.0	409.0	72934	5.0	.0	2E1&	3.97	.31	.19	.96	1.39				3 27	31	.04		.17			
409.0	414.0	72935	5.0	.0	2E89	4.46	.28	2.14	3.75	6.20				3 27	31	.04		.17			
414.0	419.0	72936	5.0	.0	2E09	4.42	.22	1.62	2.79	6.20				6 32	38	.02		.28			
419.0	424.0	72937	5.0	.0	2E89	4.15	.35	.91	1.06	5.50				6 32	38	.05		.28			
424.0	429.0	72938	5.0	.0	2E89	4.69	.26	1.31	2.06	6.20				6 32	38	.02		.28			
429.0	434.0	72939	5.0	.0	2E09	4.34	.23	.02	1.52	7.49				6 32	38	.02		.28			
434.0	439.0	72940	5.0	.0	2E1	3.81	.16	1.30	1.10	5.50				1 22	24	.04		.05			
439.0	444.0	72941	5.0	.0	2D45	3.87	.08	2.72	5.20					1 22	24	.07		.05			
444.0	449.0	72942	5.0	.0	2E1	3.97	.17	1.28	2.77	36.29				1 22	24	.05		.05			
449.0	454.0	72943	5.0	.0	2D4	3.43	.14	1.72	8.56	22.60				1 22	24	.07		.05			
454.0	459.0	72944	5.0	.0	2D4	3.70	.11	3.72	6.95	41.10				3 22	26	.07		.13			
459.0	464.0	72945	5.0	.0	2E1&	3.87	.29	.23	.95	3.39				3 22	26	.02		.13			
464.0	469.0	72946	5.0	.0	2F08	3.97	.16	1.39	6.94					3 22	26	.04		.13			
469.0	474.0	72947	5.0	.0	2E1	3.58	.14	.16	1.12	6.79				3 22	26	.05		.13			
474.0	479.0	72948	5.0	.0	2E1	3.49	.20	.23	1.06					3 26	29	.05		.17			
479.0	484.0	72949	5.0	.0	2E19	4.29	.29	.10	1.64	2.70				3 26	29	.04		.17			
484.0	489.0	72950	5.0	.0	2E19	4.02	.34	.11	.71					3 26	29	.02		.17			
489.0	494.0	72951	5.0	.0	2E19	4.37	.28	.08	1.30	2.70				3 26	29	.02		.17			
494.0	499.0	72952	5.0	.0	2E19	4.15	.34	.05	1.17	6.20				4 30	34	.04		.17			
499.0	504.0	72953	5.0	.0	2E19	4.08	.47	.41	.52	8.90				4 30	34	.04		.17			
504.0	509.0	72954	5.0	.0	2E19	3.91	.66	.51	1.33	4.09				4 30	34	.02		.17			
509.0	514.0	72955	5.0	.0	2E19	4.37	.62	.48	1.35					4 30	34	.02		.17			
514.0	519.0	72956	5.0	.0	2E19	4.08	.56	.57	2.68	13.69				2 31	34	.02		.08			
519.0	524.0	72957	5.0	.0	2E19	4.30	.14	.91	2.39	8.19				2 31	34	.11		.08			
524.0	529.0	72958	5.0	.0	2E19	4.29	.10	.29	1.56	7.49				1 32	34	.14		.01			
529.0	534.0	72959	5.0	.0	2E19	4.15	.10	.73	1.80	14.40				1 32	34	.14		.01			
534.0	539.0	72960	5.0	.0	2F4	4.21	.04	3.60	7.79	13.69					30 31	.14		.02			
539.0	544.0	72961	5.0	.0	2D4	5.04	.05	3.08	6.42	21.89					30 31	.13		.02			
544.0	549.0	72962	5.0	.0	2E4	3.37	.02	3.02	7.49	20.60					30 31	.14		.02			
549.0	554.0	72963	5.0	.0	2E4	4.61	.02	.91	3.58	9.59					30 31	.14		.02			
554.0	559.0	72964	5.0	.0	2D0	2.91	.13	.82	3.41	8.19				3 11	14	.23		.01			
559.0	564.0	72965	5.0	.0	2A13	3.06	.04	.90	2.37	6.20				3 11	14	.19		.01			
564.0	569.0	72966	5.0	.0	2A13	3.10	.04	.65	2.12	8.19				3 11	14	.17		.01			
569.0	574.0	72967	5.0	.0	2D0	3.22	.11	.90	3.58	15.80				3 11	14	.14		.01			
574.0	579.0	72968	5.0	.0	2A14	2.89	.05	1.89	4.44	29.39				1 7	9	.17		.02			

DDH: 75-09 UTM-N: 9365.1 UTM-E: 14773.7 UTM-ELEV: 4063.7 TOTAL DEPTH: 723.0 SECTION: 119+000
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

-----DEPTHS-----						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
579.0	584.0	72969	5.0	.0	2A14	3.29	.04	1.96	3.58	24.00			1	7	9	.17		.02			
584.0	589.0	72970	5.0	.0	2A0	2.93	.07	.86	2.64	15.09			1	7	9	.23		.02			
589.0	594.0	72971	5.0	.0	2A0	2.81	.05	.80	2.64	11.00			1	7	9	.23		.02			
594.0	599.0	72972	5.0	.0	2A0	2.93	.05	.40	1.69	11.00			1	6	7	.20		.02			
599.0	609.0	72973	10.0	.0	2A0	2.91	.05	.71	1.74	18.50			1	6	7	.20		.02			
609.0	614.0	72974	5.0	.0	2A0	2.87	.05	.59	2.02	13.69			1	6	7	.20		.02			
614.0	619.0	72975	5.0	.0	2A0	2.95	.05	.49	2.02	15.80			2	7	10	.22		.02			
619.0	624.0	72976	5.0	.0	2D0	3.00	.14	1.39	2.87	28.10			2	7	10	.20		.02			
624.0	629.0	72977	5.0	.0	2A0	3.00	.17	.28	1.06	11.59			2	7	10	.17		.02			
629.0	634.0	72978	5.0	.0	2A0	2.85	.05	.34	.34	18.50			2	7	10	.20		.02			
634.0	639.0	72979	5.0	.0	2A0	3.06	.08	1.64	1.28	20.60			12	2	14	.16		.04			
639.0	644.0	72980	5.0	.0	2C75	3.04	.20	.28	.62	12.30			12	2	14	.14		.04			
644.0	649.0	72981	5.0	.0	2C75	3.02	.16	1.69	2.27	21.89			12	2	14	.14		.04			
649.0	654.0	72982	5.0	.0	2A7	3.00	.13	1.52	3.00	15.09			12	2	14	.11		.04			
654.0	659.0	72983	5.0	.0	2A7	3.00	.17	.26	.07	11.00			10	1	12	.14		.02			
659.0	664.0	72984	5.0	.0	2C7	3.25	.17	3.10	6.25	34.29			10	1	12	.19		.02			
664.0	669.0	72985	5.0	.0	1D21	2.79	.10	1.04	.67	28.80			10	1	12	.23		.02			
669.0	674.0	72986	5.0	.0	1D21	2.89	.10	.24	.80	9.59			10	1	12	.23		.02			
674.0	679.0	72987	5.0	.0	1D21	2.91	.08	1.01	1.82	17.80			4	3	7	.20		.01			
679.0	684.0	72988	5.0	.0	2A0	2.91	.08	1.35	1.37	17.10			4	3	7	.14		.01			
684.0	689.0	72989	5.0	.0	2L@	2.85	.11	.62	1.78	10.30			4	3	7	.14		.01			
689.0	694.0	72990	5.0	.0	2D0&	2.93	.08	3.02	4.20	67.50			4	3	7	.11		.01			
694.0	699.0	72991	5.0	.0	2D0&	3.00	.13	2.47	3.16	38.39			3	3	6	.08					
699.0	704.0	72992	5.0	.0	1D4	2.91	.05	3.37	5.05	40.50			3	3	6	.13					
704.0	709.0	72993	5.0	.0	2A0	2.85	.02	1.03	1.87	14.40			3	3	6	.16					

DDH: 75-10 UTM-N: 9302.4 UTM-E: 15100.8 UTM-ELEV: 4141.0 TOTAL DEPTH: 957.0 SECTION: 121+000
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

-----DEPTHS-----						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
485.0	490.0	72996	5.0	.0	2D35	3.31	.05	1.73	4.62	13.00				2 14	17	.11		.01			
490.0	495.0	72997	5.0	.0	2D35	3.35	.05	1.39	3.72	8.19				1 22	24	.11		.01			
495.0	500.0	72998	5.0	.0	2D35	3.37	.04	1.43	3.72	26.69				1 16	18	.11		.02			
500.0	505.0	72999	5.0	.0	2D35	3.35	.07	1.05	4.21	15.09				1 16	18	.11		.02			
505.0	510.0	73000	5.0	.0	2D35	2.91	.04	1.69	5.20	7.49				1 16	18	.10		.02			
510.0	515.0	73001	5.0	.0	2D35	4.09	.02	1.87	3.29	21.30					16 17	.11		.01			
515.0	520.0	73002	5.0	.0	2D35	3.02	.05	1.85	5.19	10.30					16 17	.11		.01			
520.0	525.0	73003	5.0	.0	2C35	3.12	.14	.35	1.10	8.90					16 17	.11		.01			
525.0	530.0	73004	5.0	.0	2C35	3.10	.08	.83	2.83	3.39					16 17	.08		.01			
530.0	535.0	73005	5.0	.0	2D35	3.41	.10	2.70	4.54	49.39					19 20	.05		.02			
535.0	540.0	73006	5.0	.0	2C35	4.06	.16	1.36	.75	21.89					19 20	.04		.02			
540.0	545.0	73007	5.0	.0	2E19	3.56	.24	.62	1.79	4.09					19 20	.04		.02			
545.0	550.0	73008	5.0	.0	2E19	3.66	.11	.31	.92	4.09					19 20	.08		.02			
550.0	555.0	73009	5.0	.0	2C35	3.62	.05	.55	1.71	9.59				1 17	18	.08		.02			
555.0	560.0	73010	5.0	.0	2C35	3.29	.05	.61	1.46	15.09				1 17	18	.13		.02			
560.0	565.0	73011	5.0	.0	2C35	3.25	.05	1.71	1.96	20.60				1 17	18	.14		.02			
565.0	570.0	73012	5.0	.0	2C35	3.25	.04	1.59	2.24	5.50				1 17	18	.16		.02			
570.0	575.0	73013	5.0	.0	2C35	3.41	.05	1.11	2.10	5.50				1 14	16	.17		.02			
575.0	580.0	73014	5.0	.0	2D50	3.35	.05	1.64	1.53	5.50				1 14	16	.14		.02			
580.0	585.0	73015	5.0	.0	2D50	3.33	.08	1.77	7.92	10.30				1 14	16	.17		.02			
585.0	590.0	73016	5.0	.0	2C35	3.27	.05	.65	2.14	9.59				1 14	16	.05		.02			
590.0	595.0	73017	5.0	.0	2C35	3.68	.08	1.04	2.37	13.69				1 20	21	.08		.02			
595.0	600.0	73018	5.0	.0	2D35	3.56	.05	3.60	7.20	20.60				1 20	21	.14		.02			
600.0	605.0	73019	5.0	.0	2C35	3.49	.04	.75	2.31	25.69				1 20	21	.11		.02			
605.0	610.0	73020	5.0	.0	2E08	3.47	.02	1.07	1.81	36.70				1 20	21	.05		.02			
610.0	613.5	73021	3.5	.0	2D4	4.05	.05	3.68	10.59	363.50				2 16	19	.07		.02			
624.5	630.0	73023	5.5	.0	2D08	3.25	.11	1.55	3.58	122.79				2 16	19	.14		.02			
630.0	635.0	73024	5.0	.0	1D40	2.99	.08	2.54	3.18	110.40				3 3	7	.14		.05			
635.0	638.0	73025	3.0	.0	2B4	3.18	.14	1.65	4.98	24.00				3 3	7	.11		.05			

DDH: 75-11 UTM-N: 8878.3 UTM-E: 14097.0 UTM-ELEV: 4000.1 TOTAL DEPTH: 2120.0 SECTION: 118+000
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

-----DEPTHS----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
477.0	480.0	73030	3.0	.0	2A0	2.95	.16	.40	.75					3	7	10	.16				.02
480.0	485.0	73031	5.0	.0	2A4	3.04	.08	1.49	2.60	8.19				3	7	10	.10				.02
485.0	490.0	73032	5.0	.0	2A4	2.60	.05	2.50	5.33	24.00				3	7	10	.14				.02
490.0	495.0	73033	5.0	.0	2A4	2.81	.15	1.60	2.93	6.20				11	11	22	.26				.02
495.0	500.0	73034	5.0	.0	2F4&	3.87	.17	3.60	6.29	33.60				11	11	22	.17				.02
500.0	505.0	73035	5.0	.0	2F4&	4.30	.31	5.50	7.08	41.79				11	11	22	.08				.02
505.0	510.0	73036	5.0	.0	2H49	3.50	.35	4.02	5.78	35.00				11	11	22	.39				.02
510.0	515.0	73037	5.0	.0	10E0	2.73	.01	.10	.08	4.79				22	5	27	.85				.01
515.0	520.0	73038	5.0	.0	2H48	3.81	.32	5.19	7.89	55.49				22	5	27	.23				.10
520.0	525.0	73039	5.0	.0	2H48	5.21	.44	6.84	9.59	41.79				22	5	27	.40				.10
525.0	530.0	73040	5.0	.0	2H48	3.89	.34	6.61	9.69	68.59				22	5	27	.46				.10
530.0	535.0	73041	5.0	.0	2H48	3.79	.44	5.50	7.58	68.59				12	21	33	.40				.10
535.0	540.0	73042	5.0	.0	2F4	4.25	.32	5.58	8.98	61.70				12	21	33	.17				.10
540.0	545.0	73043	5.0	.0	2F4	4.62	.08	4.90	8.10	54.89				12	21	33	.11				.10
545.0	550.0	73044	5.0	.0	2F4	4.00	.11	4.96	7.78	60.39				12	21	33	.08				.10
550.0	555.0	73045	5.0	.0	2H48	4.17	.64	4.98	7.17	58.29				21	7	28	.41				.08
555.0	560.0	73046	5.0	.0	2D79	3.31	.23	2.02	5.23	35.00				21	7	28	.14				.08
560.0	565.0	73047	5.0	.0	2H49	3.60	.61	4.09	7.09	76.09				21	7	28	.10				.08
565.0	570.0	73048	5.0	.0	2H49	3.79	.49	3.89	4.59	96.70				21	7	28	1.74				.08

DDH: 75001 UTM-N: 9431.1 UTM-E: 14149.0 UTM-ELEV: 3832.3 TOTAL DEPTH: 233.0 SECTION:
 RFE: RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
39.0	42.0	72643	3.0	.0	****	3.00	.28	5.93	6.61	118.60				8 12	21	.02		.07			
42.0	47.0	72644	5.0	.0	****	2.96	.38	1.60	2.87	19.20				8 12	21	.02		.07			
47.0	52.0	72645	5.0	.0	****	2.96	.22	1.27	1.52	13.70				8 12	21	.03		.07			
52.0	57.0	72646	5.0	.0	****	3.26	.45	.08	.12					8 12	21	.02		.07			
57.0	62.0	72647	5.0	.0	****	3.23	.41	.37	.38	1.70				8 12	21	.03		.07			
62.0	67.0	72648	5.0	.0	****	3.51	.29	.31	.56	1.40				10 13	23	.02		.11			
67.0	72.0	72649	5.0	.0	****	3.17	.27	.02	.16					10 13	23	.02		.11			
72.0	77.0	72650	5.0	.0	****	3.05	.24	.10	.13					10 13	23	.16		.11			
77.0	82.0	72651	5.0	.0	****	3.67	.28	2.48	2.60	21.20				10 13	23	3.79		.11			
82.0	87.0	72652	5.0	.0	****	4.15	.40	5.01	7.00	92.60				10 21	31	.18		.32			
87.0	92.0	72653	5.0	.0	****	4.59	.18	4.93	6.30	113.80				10 21	31	3.43		.32			
92.0	97.0	72654	5.0	.0	****	4.60	.15	7.39	6.40	87.80				10 21	31	16.17		.32			
97.0	102.0	72655	5.0	.0	****	4.46	.23	5.71	6.00	87.10				10 21	31	8.67		.32			
102.0	107.0	72656	5.0	.0	****	4.62	.13	5.24	5.25	53.50				1 33	35	20.49		.06			
107.0	112.0	72657	5.0	.0	****	4.71	.16	3.30	5.48	43.90				1 33	35	.20		.06			
112.0	117.0	72658	5.0	.0	****	4.14	.14	1.77	2.00	32.20				1 33	35	.04		.06			
117.0	122.0	72659	5.0	.0	****	4.63	.30	2.23	1.70	24.70				1 33	35	.02		.06			
122.0	127.0	72660	5.0	.0	****	4.71	.33	2.54	2.89	17.10				4 33	38	.01		.17			
127.0	132.0	72661	5.0	.0	****	4.51	.49	1.86	2.94	28.10				4 33	38	.02		.17			
132.0	137.0	72662	5.0	.0	****	4.78	.26	3.98	3.78	43.90				4 33	38	1.78		.17			
137.0	142.0	72663	5.0	.0	****	4.45	.20	2.63	2.73	34.30				4 33	38	4.13		.17			
142.0	147.0	72664	5.0	.0	****	4.02	.17	1.31	1.30	10.30				3 31	34	.03		.10			
147.0	152.0	72665	5.0	.0	****	4.28	.11	1.95	2.32	12.30				3 31	34	.02		.10			
152.0	157.0	72666	5.0	.0	****	4.36	.21	3.05	3.25	27.40				3 31	34	5.11		.10			
157.0	162.0	72667	5.0	.0	****	4.65	.27	4.80	4.98	61.70				3 31	34	4.64		.10			
162.0	167.0	72668	5.0	.0	****	4.58	.20	3.35	4.13	24.70				4 34	38	.05		.14			
167.0	172.0	72669	5.0	.0	****	4.61	.19	6.39	11.30	30.90				4 34	38	.05		.14			
172.0	177.0	72670	5.0	.0	****	4.61	.69	.56	1.52	12.30				4 34	38	.02		.14			
177.0	182.0	72671	5.0	.0	****	4.71	.40	2.30	3.60	9.60				4 34	38	.01		.14			
182.0	187.0	72672	5.0	.0	****	4.52	.68	1.58	2.40	13.00				2 35	37	.01		.05			
187.0	192.0	72673	5.0	.0	****	4.69	.34	2.42	4.94	12.30				2 35	37	.02		.05			
192.0	197.0	72674	5.0	.0	****	4.12	.57	4.44	3.44	31.50				2 35	37	.05		.05			
197.0	202.0	72675	5.0	.0	****	4.74	.17	3.90	7.20	26.70				2 35	37	.03		.05			
202.0	207.0	72676	5.0	.0	****	4.61	.33	4.63	6.52	25.40				1 33	34	.02		.03			
207.0	212.0	72677	5.0	.0	****	4.55	.30	2.75	3.58	21.90				1 33	34	.03		.03			
212.0	217.0	72678	5.0	.0	****	4.11	.36	3.17	4.78	25.40				1 33	34	.05		.03			
217.0	222.0	72679	5.0	.0	****	4.32	.20	2.72	7.40	18.50				1 33	34	.04		.03			
222.0	227.0	72680	5.0	.0	****	2.77	.07	1.25	3.10	17.10				2 5	7	.07		.02			
227.0	233.0	72681	6.0	.0	****	2.75	.14	1.28	2.43	35.00				2 5	7	.07		.02			

DDH: 75002 UTM-N: 8997.7 UTM-E: 14399.9 UTM-ELEV: 4025.5 TOTAL DEPTH: 687.0 SECTION: 119+000
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

-----DEPTHS-----						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
513.5	515.0	72684	1.5	.0	2H49	4.33	.68	5.74	7.65	91.20			9	25	35	.30		.29			
515.0	520.0	72685	5.0	.0	2F4	4.70	.17	6.60	7.24	96.00			9	25	35	.02		.29			
520.0	525.0	72686	5.0	.0	2F4	5.63	.08	5.98	7.44	71.30			9	25	35	.99		.29			
525.0	530.0	72687	5.0	.0	2H469	4.44	.36	5.60	7.21	58.30			9	25	35	2.03		.29			
530.0	535.0	72688	5.0	.0	2E4(2	4.79	.31	4.57	6.58	50.10			16	21	38	1.00		.25			
535.0	540.0	72689	5.0	.0	2F467	4.60	.11	5.66	6.30	69.30			16	21	38	5.64		.25			
540.0	545.0	72690	5.0	.0	2H49	4.50	.41	4.86	5.80	54.90			16	21	38	.39		.25			
545.0	550.0	72691	5.0	.0	2H49(	5.80	.35	5.42	7.10	59.00			16	21	38	1.84		.25			
550.0	555.0	72692	5.0	.0	2H49(	5.76	.36	5.94	6.36	78.90			13	24	38	5.30		.42			
555.0	560.0	72693	5.0	.0	2H496	4.39	.65	4.44	4.49	52.10			13	24	38	1.08		.42			
560.0	565.0	72694	5.0	.0	2E489	4.55	.24	3.72	4.15	37.00			13	24	38	.66		.42			
565.0	570.0	72695	5.0	.0	2E49	4.59	.28	3.14	3.00	42.50			13	24	38	.74		.42			
570.0	575.0	72696	5.0	.0	2F69(	4.76	.33	3.52	3.47	58.30			13	24	38	1.28		.42			
575.0	580.0	72697	5.0	.0	2D9(2	3.88	.43	3.16	3.12	48.00			3	29	32	3.17		.11			
580.0	585.0	72698	5.0	.0	2F0	4.61	.09	4.23	5.02	44.60			3	29	32	.15		.11			
585.0	590.0	72699	5.0	.0	2G4	5.36	.19	5.64	6.38	52.80			3	29	32	17.16		.11			
590.0	595.0	72700	5.0	.0	2E0	4.71	.10	2.42	1.40	15.80			3	29	32	.05		.11			
595.0	600.0	72701	5.0	.0	2E9	4.73	.31	2.44	1.85	15.80			11	17	29	.05		.10			
600.0	605.0	72702	5.0	.0	2D9	3.41	.41	1.42	3.90	17.80			11	17	29	.08		.10			
605.0	610.0	72703	5.0	.0	2H09	3.25	.62	1.90	3.40	25.40			11	17	29	.21		.10			
610.0	615.0	72704	5.0	.0	2D459	4.40	.28	3.10	7.12	47.30			11	17	29	.12		.10			
615.0	620.0	72705	5.0	.0	2A0	2.76	.04	.81	2.56	10.30			3	20	23	.22		.02			
620.0	625.0	72706	5.0	.0	2E4	4.03	.03	2.42	7.70	26.10			3	20	23	.09		.02			
625.0	630.0	72707	5.0	.0	2E4	5.55	.04	1.81	6.54	8.20			3	20	23	.10		.02			
630.0	635.0	72708	5.0	.0	2E4	3.86	.15	3.46	6.40	22.60			3	20	23	.10		.02			
635.0	640.0	72709	5.0	.0	2D459	2.90	.22	.40	7.25	11.00			12	2	14	.14		.03			
640.0	645.0	72710	5.0	.0	2A4	2.67	.11	.81	3.32	16.40			12	2	14	.14		.03			
645.0	650.0	72711	5.0	.0	2A4	2.70	.10	1.27	3.10	17.10			12	2	14	.14		.03			
650.0	654.7	72712	4.7	.0	2A49	3.83	1.11	2.12	4.25	56.90			12	2	14	.06		.03			

DDH: 75007 UTM-N: 9856.4 UTM-E: 14432.6 UTM-ELEV: 3906.0 TOTAL DEPTH: 261.0 SECTION:
 RFE: RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	Ba0 %	Hg %	Mn %	As %	Ba %
49.0	50.0	72842	1.0	.0	****	3.56	.24	.20	.05	11.00			2	22	24	.03		.02		
50.0	55.0	72843	5.0	.0	****	3.36	.12	.18	.96	2.00			2	22	24	.04		.02		
55.0	60.0	72844	5.0	.0	****	3.58	.17	.76	2.20	2.00			1	26	28	.02		.02		
60.0	65.0	72845	5.0	.0	****	3.66	.06	4.55	3.71	87.80			1	26	28	.03		.02		
65.0	70.0	72846	5.0	.0	****	4.03	.04	2.23	4.62	8.90			1	26	28	.03		.02		
70.0	75.0	72847	5.0	.0	****	3.64	.04	1.94	4.00	8.90			1	26	28	.05		.02		
75.0	80.0	72848	5.0	.0	****	3.73	.04	1.12	3.00	8.90			1	22	24	.04		.01		
80.0	85.0	72849	5.0	.0	****	3.49	.05	1.76	4.14	11.00			1	22	24	.08		.01		
85.0	90.0	72850	5.0	.0	****	3.51	.06	1.78	4.38	17.10			1	22	24	.04		.01		
90.0	95.0	72851	5.0	.0	****	3.50	.04	1.50	4.85	13.70			1	22	24	.06		.01		
95.0	100.0	72852	5.0	.0	****	3.41	.03	.25	1.49	4.80			2	17	19	.06		.02		
100.0	105.0	72853	5.0	.0	****	3.46	.05	3.76	4.20	30.90			2	17	19	.06		.02		
105.0	110.0	72854	5.0	.0	****	3.22	.03	1.12	4.73	17.10			2	17	19	.07		.02		
110.0	115.0	72855	5.0	.0	****	3.27	.03	1.50	4.53	17.10			2	17	19	.06		.02		
115.0	120.0	72856	5.0	.0	****	3.44	.04	.23	1.48	6.80			1	19	21	.08		.01		
120.0	125.0	72857	5.0	.0	****	3.43	.07	1.30	5.16	17.10			1	19	21	.05		.01		
125.0	130.0	72858	5.0	.0	****	3.36	.05	1.88	6.58	11.00			1	19	21	.08		.01		
130.0	135.0	72859	5.0	.0	****	3.44	.02	.26	.53	8.90			1	19	21	.07		.01		
135.0	140.0	72860	5.0	.0	****	3.37	.04	1.88	4.05	21.20			1	18	19	.11		.01		
140.0	145.0	72861	5.0	.0	****	3.44	.03	1.01	1.16	13.70			1	18	19	.08		.01		
145.0	150.0	72862	5.0	.0	****	3.53	.05	.72	.91	8.20			1	18	19	.06		.01		
150.0	155.0	72863	5.0	.0	****	3.27	.04	3.09	3.22	37.70			1	18	19	.08		.01		
155.0	160.0	72864	5.0	.0	****	3.39	.03	.33	1.18	10.30			1	15	17	.08		.01		
160.0	165.0	72865	5.0	.0	****	3.25	.04	1.50	2.78	3.40				15	15	.06		.01		
165.0	170.0	72866	5.0	.0	****	3.22	.06	.67	4.50	15.40				15	15	.08		.01		
170.0	175.0	72867	5.0	.0	****	3.31	.04	.42	1.93	8.90			1	15	17	.03		.01		
175.0	180.0	72868	5.0	.0	****	3.29	.07	1.74	3.21	12.30			2	17	19	.07		.01		
180.0	185.0	72869	5.0	.0	****	3.12	.06	1.87	4.48	21.90			2	17	19	.09		.01		
185.0	190.0	72870	5.0	.0	****	2.87	.04	1.35	2.10	22.60			2	17	19	.06		.01		
190.0	195.0	72871	5.0	.0	****	4.02	.02	6.02	12.60	47.30			2	17	19	.02		.01		
195.0	200.0	72872	5.0	.0	****	4.72	.02	6.05	12.20	51.40			1	36	38	.01		.01		
200.0	205.0	72873	5.0	.0	****	4.76	.01	1.91	6.38	28.80			1	36	38			.01		
205.0	210.0	72874	5.0	.0	****	4.79	.02	1.20	6.25	15.10			1	36	38	.02		.01		
210.0	215.0	72875	5.0	.0	****	4.85	.02	3.53	7.31	32.90			1	36	38	.01		.01		
215.0	220.0	72876	5.0	.0	****	4.67	.03	7.45	17.20	63.80			3	14	17			.04		
220.0	225.0	72877	5.0	.0	****	3.22	.24	.67	5.27	10.30			3	14	17	.05		.04		
225.0	230.0	72878	5.0	.0	****	3.14	.10	.50	2.00	14.40			3	14	17	.04		.04		
230.0	235.0	72879	5.0	.0	****	2.89	.15	.35	.44	8.60			3	14	17	.09		.04		
235.0	240.0	72880	5.0	.0	****	2.84	.09	.76	.82	16.10			3	4	8	.12		.05		
240.0	245.0	72881	5.0	.0	****	2.79	.07	.35	.07	3.40			3	4	8	.08		.05		
245.0	250.0	72882	5.0	.0	****	2.99	.18	.45	2.27	5.10			3	4	8	.06		.05		
250.0	255.0	72883	5.0	.0	****	3.05	.19	1.12	3.70	19.50			3	4	8	.07		.05		
255.0	261.0	72884	6.0	.0	****	3.18	.15	2.52	5.18	39.10			3	4	8	.04		.05		

PAGE: 105

[illegible]

PAGE : 106

DDH: 75456-15 UTM-N: 6791.0 UTM-E: 14397.0 UTM-ELEV: 4018.0 TOTAL DEPTH: 821.0 SECTION: 130
RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

[illegible]

PAGE: 107

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	---ASSAYS---													
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %
720.0	724.5	04244	4.5	.0	2H4	.22	5.03	8.13	85.00			.20								
724.5	729.5	04245	5.0	.0	1D/2H	.07	4.20	.19	263.70											
729.5	734.0	04246	4.5	.0	2C0	.08	.68	1.91	30.19											
734.0	739.0	04247	5.0	.0	2D0	.10	1.96	3.35	47.29											
739.0	743.0	04248	4.0	.0	2E4	.28	4.95	7.61	100.09			.20								
743.0	748.0	04249	5.0	.0	2B4	.08	1.64	3.41	28.49											
748.0	753.0	04250	5.0	.0	2L1	.05	.02	.02	.29											
753.0	758.0	04501	5.0	.0	1D0	.02	.01	.01	.29											
758.0	762.5	04502	4.5	.0	1D0	.05	.48	.01	27.10											
762.5	766.5	04503	4.0	.0	1D0	.08	.08	.01	.10											
766.5	771.5	04504	5.0	.0	2H4	.41	5.25	6.44	134.09			.20								

DDH: 76-01 UTM-N: 9067.7 UTM-E: 15135.1 UTM-ELEV: 4185.6 TOTAL DEPTH: 754.0 SECTION: 122+020
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

-----DEPTHS-----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
607.4	609.0	73057	1.6	.0	2C9	2.99	.41	1.02	2.72	24.30			6	12	18	.16		.10			
609.0	611.0	73058	2.0	.0	2C9	3.41	.59	.80	.46	27.39			6	12	18	.08		.10			
611.0	613.0	73059	2.0	.0	2D39	3.33	.41	3.49	1.38	52.10			6	12	18	.08		.10			
613.0	614.2	73060	1.2	.0	2D39	3.08	.29	2.02	3.16	21.60			6	12	18	.11		.10			
614.2	614.8	73061	.6	.0	2D3	3.47	.14	1.43	3.58	8.19			6	12	18	.10		.10			
614.8	616.0	73062	1.2	.0	2D3	3.91	.05	8.16	18.10	32.60			6	12	18	.14		.10			
616.0	616.5	73063	.5	.0	2D3	3.75	.17	3.47	2.85	17.80			6	12	18	.05		.10			
616.5	616.8	73064	.3	.0	1E19	2.99	.10	.29	.23	8.19			6	12	18	.35		.10			
616.8	617.2	73065	.4	.0	1E19	2.98	.13	.39	.10	8.90			6	12	18	.22		.10			
617.2	617.4	73066	.2	.0	2D39	4.46	.07	8.65	9.16	39.79			6	12	18	.08		.10			
617.4	618.3	73067	.9	.0	2D3	3.81	.23	8.04	10.90	41.79			6	12	18	.08		.10			
618.3	618.9	73068	.6	.0	2D3	3.54	.13	2.73	4.05	21.19			6	12	18	.08		.10			
618.9	619.6	73069	.7	.0	2C0	3.37	.14	.35	.27	16.39			6	12	18	.08		.10			
619.6	619.9	73070	.3	.0	1D4	2.91	.04	.14	.23				2	16	19	.14		.02			
619.9	621.0	73071	1.1	.0	1D4	2.87	.02	.11	.19				2	16	19	.16		.02			
621.0	621.7	73072	.7	.0	1D4	3.29	.10	.16	.38	7.90			2	16	19	.13		.02			
621.7	623.0	73073	1.3	.0	2C0	3.49	.10	.99	1.96	12.30			2	16	19	.10		.02			
623.0	623.5	73074	.5	.0	2D35	3.47	.04	1.17	3.29	8.59			2	16	19	.13		.02			
623.5	626.4	73075	2.9	.0	2D35	3.47	.05	2.41	3.37	11.59			2	16	19	.11		.02			
626.4	631.4	73076	5.0	.0	2C53	3.62	.11	.99	2.17				2	16	19	.08		.02			
631.4	636.4	73077	5.0	.0	2D35	3.43	.05	1.74	5.96	9.59			2	16	19	.11		.02			
636.4	639.4	73078	3.0	.0	2D35	3.54	.05	1.99	5.94	10.30			2	16	19	.11		.02			
639.4	640.7	73079	1.3	.0	2C35	3.39	.04	.93	2.35				2	16	19	.11		.02			
640.7	645.7	73080	5.0	.0	2D35	3.37	.11	1.37	2.60	15.80			2	20	22	.11		.02			
645.7	650.7	73081	5.0	.0	2C35	3.47	.07	.47	3.20				2	20	22	.13		.02			
650.7	655.7	73082	5.0	.0	2C35	3.68	.10	.61	1.34				2	20	22	.10		.02			
655.7	660.0	73083	4.3	.0	2C3	3.85	.13	.54	1.35	4.79			2	20	22	.05		.02			
660.0	661.0	73084	1.0	.0	2C3	3.87	.08	.08	.69	6.79			2	20	22	.08		.02			
661.0	665.0	73085	4.0	.0	2C3	4.15	.29	.44	1.39	3.39			3	24	27	.05		.02			
665.0	666.0	73086	1.0	.0	2E4	4.33	.17	1.95	5.48				3	24	27	.02		.02			
666.0	669.0	73087	3.0	.0	2C3	3.89	.11	.41	.62	7.49			3	24	27	.05		.02			
669.0	671.0	73088	2.0	.0	2A3I	3.47	.04	1.28	1.60	8.19			3	24	27	.17		.02			

DDH: 76-02 UTM-N: 8892.2 UTM-E: 15099.2 UTM-ELEV: 4181.5 TOTAL DEPTH: 821.0 SECTION: 123+015
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

-----DEPTHS-----						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
582.7	583.7	73094	1.0	.0	2D49	3.47	.28	2.93	8.30	47.29			4	13	18	.46		.17			
583.7	586.5	73095	2.8	.0	2G4	4.54	.02	2.89	6.13	120.29			4	13	18	39.25		.17			
586.5	591.5	73096	5.0	.0	2G4(	4.55	.10	6.29	5.70	66.20			4	13	18	32.95		.17			
591.5	596.5	73097	5.0	.0	2G4(	4.50	.14	3.74	3.14	88.79			3	21	25	13.00		.16			
596.5	601.5	73098	5.0	.0	2G4(	4.84	.11	6.04	6.75	81.90			3	21	25	25.67		.16			
601.5	606.5	73099	5.0	.0	2G4(	4.63	.14	6.63	7.26	46.60			3	21	25	28.19		.16			
606.5	611.5	73100	5.0	.0	2G4(	4.61	.10	4.25	7.58	13.69			3	21	25	12.60		.16			
611.5	616.5	73101	5.0	.0	2C3(	4.16	.05	.83	1.26	40.79			2	30	32	.08		.02			
616.5	621.2	73102	4.7	.0	2C3	3.74	.05	.58	.29	20.19			2	30	32	.19		.02			
621.2	626.3	73103	5.1	.0	2E4(	4.59	.32	4.54	4.34	18.19			2	30	32	.19		.02			
626.3	630.0	73104	3.7	.0	2E19	3.95	.23	1.52	.77	40.79			2	30	32	.17		.02			
630.0	631.5	73105	1.5	.0	2E41	4.50	.10	5.13	4.90	27.10			2	30	32	.02		.02			
631.5	639.8	73106	8.3	.0	2E4(	4.36	.07	2.64	5.65	60.29			12	22	34	.75		.07			
639.8	640.5	73107	.7	.0	2H4	3.95	.17	3.89	8.65	76.79			12	22	34	.63		.07			
640.5	641.5	73108	1.0	.0	2D49	3.35	.29	3.97	13.00	69.29			12	22	34	.61		.07			
641.5	643.8	73109	2.3	.0	2H49	4.40	.46	4.59	7.70	63.10			12	22	34	2.79		.07			
643.8	646.5	73110	2.7	.0	2E4(	4.44	.02	3.10	5.54	34.79			12	22	34	3.76		.07			
646.5	648.0	73111	1.5	.0	2E49	4.33	.35	2.24	4.95	30.19			12	22	34	4.54		.07			
648.0	651.4	73112	3.4	.0	2H39	3.79	.40	.63	1.99	14.40			12	22	34	.31		.07			
651.4	656.5	73113	5.1	.0	2E19	4.17	.39	.27	.69	13.69			2	30	32	.02		.02			
656.5	661.5	73114	5.0	.0	2E19	4.30	.56	.90	1.37	20.89			2	30	32	.01		.02			
661.5	665.5	73115	4.0	.0	2C9	3.64	.28	.16	.78	10.59			2	30	32	.04		.02			
665.5	671.5	73116	6.0	.0	2C0	3.81	.08	.56	.97	16.39			2	30	32	.04		.02			
671.5	676.5	73117	5.0	.0	2E9&	4.29	.28	.28	1.23	7.49			2	33	35	.02		.02			
676.5	677.7	73118	1.2	.0	2E9&	4.46	.27	.05	.94	7.49			2	33	35	.02		.02			
677.7	682.0	73119	4.3	.0	2C5(	4.30	.11	.45	1.99	8.19			2	33	35	.02		.02			
682.0	686.5	73120	4.5	.0	2C0	3.64	.08	.14	1.69	7.49			2	33	35	.08		.02			
686.5	691.5	73121	5.0	.0	2C9	4.84	.59	.90	1.67				2	33	35	.05		.02			
691.5	696.5	73122	5.0	.0	2C9	4.65	.52	.90	1.35	12.00			3	30	34	.02		.08			
696.5	701.5	73123	5.0	.0	2C9(	4.84	.48	1.08	1.64	13.69			3	30	34	.01		.08			
701.5	706.5	73124	5.0	.0	2C9	4.37	.40	2.16	1.57	22.60			3	30	34	.05		.08			
706.5	709.0	73125	2.5	.0	2C9	3.87	.48	1.16	.84	11.59			3	30	34	.04		.08			
709.0	711.5	73126	2.5	.0	2E89	4.90	.32	.54	1.77	6.90			3	30	34	.02		.08			
711.5	715.1	73127	3.6	.0	2E48	4.42	.17	3.58	3.70	23.30			10	23	33	.02		.20			
715.1	716.5	73128	1.4	.0	2E31	3.91	.28	.49	1.83	11.00			10	23	33	.02		.20			
716.5	721.5	73129	5.0	.0	2E31	3.68	.41	.20	.99	9.90			10	23	33	.02		.20			
721.5	726.8	73130	5.3	.0	2C3(	4.17	.14	2.45	1.46	17.10			10	23	33	.02		.20			
726.8	731.5	73131	4.7	.0	2E39	3.66	.20	.14	.34	1.39			10	23	33	.02		.20			
731.5	735.2	73132	3.7	.0	2E39	3.54	.23	.51	1.94	12.69			7	19	27	.07		.17			
735.2	736.5	73133	1.3	.0	2D0	3.58	.07	3.00	4.58	40.79			7	19	27	.10		.17			
736.5	742.0	73134	5.5	.0	2C9(	3.50	.24	.68	2.89	27.39			7	19	27	.08		.17			
742.0	747.1	73135	5.1	.0	2C9	3.76	.20	.40	1.32				7	19	27	.02		.17			
747.1	751.5	73136	4.4	.0	2E89	4.15	.89	.17	1.08	6.79			7	19	27	.01		.17			
751.5	756.5	73137	5.0	.0	2C9(	4.01	.31	.11	1.03	22.60			6	26	32	.01		.13			
756.5	761.5	73138	5.0	.0	2C9(	4.26	.34	.28	.28				6	26	32	.01		.13			
761.5	766.5	73139	5.0	.0	2E89	4.34	.62	.28	.41	57.20			6	26	32	.01		.13			
766.5	771.5	73140	5.0	.0	2E89	4.50	.61	.23	.52	3.39			6	26	32	.02		.13			
771.5	776.5	73141	5.0	.0	2C39	4.69	.40	2.35	3.74	6.79			6	29	35	.01		.14			
776.5	781.5	73142	5.0	.0	2E89	4.74	.26	1.78	2.75	40.79			6	29	35	.01		.14			
781.5	786.5	73143	5.0	.0	2E89	4.46	.59	.56	1.73	11.40			6	29	35	.02		.14			
786.5	791.5	73144	5.0	.0	2E89	4.21	.39	.48	1.20				6	29	35	.05		.14			

DDH: 76-02 UTM-N: 8892.2 UTM-E: 15099.2 UTM-ELEV: 4181.5 TOTAL DEPTH: 821.0 SECTION: 123+015
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

-----DEPTHS-----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
791.5	792.7	73145	1.2	.0	2E8&	4.05	.13	.75	1.18				5	8	13	.02		.05			
792.7	793.4	73146	.7	.0	2D4	3.41	.17	4.26	11.69	26.39			5	8	13	.01		.05			
793.4	796.5	73147	3.1	.0	2B0	2.95	.14	.68	.94	58.20			5	8	13	.10		.05			
796.5	801.5	73148	5.0	.0	2B0(	3.37	.20	5.15	1.63	238.99			5	8	13	.05		.05			
801.5	805.5	73149	4.0	.0	2C0(	3.06	.13	2.39	5.29	14.40			5	8	13	.10		.05			

DDH: 76-03 UTM-N: 8798.3 UTM-E: 15009.1 UTM-ELEV: 4166.0 TOTAL DEPTH: 866.0 SECTION: 123+015
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	---ASSAYS---														
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
582.0	586.0	73154	4.0	.0	2H43	4.08	.28	2.91	5.50	32.19			14	12	27	7.54		.11			
586.0	591.0	73155	5.0	.0	2D47	3.77	.22	4.45	6.90	70.59			14	12	27	2.14		.11			
591.0	594.5	73156	3.5	.0	2D43	3.76	.28	5.58	8.15	28.80			14	12	27	2.60		.11			
594.5	598.8	73157	4.3	.0	2G4	4.32	.05	5.00	6.45	98.70			14	12	27	33.67		.11			
598.8	603.0	73158	4.2	.0	2K0?	2.54	.04	.10	.08	85.70			4	19	23	.20		.11			
603.0	605.8	73159	2.8	.0	2G49	4.34	.20	5.62	4.90	93.20			4	19	23	27.91		.11			
605.8	607.3	73160	1.5	.0	2E4	4.79	.05	3.04	4.95	29.49			4	19	23	.66		.11			
607.3	611.0	73161	3.7	.0	2G4	4.87	.05	4.59	8.90	42.50			4	19	23	26.75		.11			
611.0	614.3	73162	3.3	.0	2G4	4.79	.14	6.79	9.08	87.79			4	19	23	10.86		.11			
614.3	616.0	73163	1.7	.0	2G4	4.66	.05	5.29	6.45	49.70			4	19	23	14.51		.11			
616.0	617.0	73164	1.0	.0	2E41	4.61	.07	5.33	8.13	48.00			4	19	23	2.52		.11			
617.0	621.0	73165	4.0	.0	2E1	3.85	.02	.20	.28	1.69			1	26	27	.04		.01			
621.0	626.0	73166	5.0	.0	2E1	3.89	.02	.11	.08	6.79			1	26	27	.04		.01			
626.0	631.0	73167	5.0	.0	2E1	3.95	.02	.14	.11	5.50			1	26	27	.04		.01			
631.0	636.0	73168	5.0	.0	2E1	3.64	.01	.31	.14	5.50			1	26	27	.05		.01			
636.0	641.0	73169	5.0	.0	2C0	3.18	.02	.11	1.14	5.50			1	26	27	.05		.01			
641.0	646.0	73170	5.0	.0	2E1	4.20	.02	1.07	.14	12.69			2	33	35	.05		.02			
646.0	650.0	73171	4.0	.0	2E1	4.33	.02	.85	.82	9.59			2	33	35	.05		.02			
650.0	651.0	73172	1.0	.0	2E41	4.83	.02	.72	3.31	13.69			2	33	35	.04		.02			
651.0	653.0	73173	2.0	.0	2E0	4.61	.04	1.13	2.29				2	33	35	.24		.02			
653.0	656.0	73174	3.0	.0	2E1	4.06	.02	.10	.17	2.70			2	33	35	.02		.02			
656.0	661.0	73175	5.0	.0	2E1	3.99	.02	.23	.22				2	33	35	.07		.02			
661.0	665.0	73176	4.0	.0	2E1	5.42	.13	1.12	1.33	13.69			2	29	32	.05		.02			
665.0	666.0	73177	1.0	.0	2E4	4.48	.11	4.12	5.38	31.49			2	29	32	.13		.02			
666.0	667.0	73178	1.0	.0	2E4	4.67	.02	5.44	6.26	39.10			2	29	32	.05		.02			
667.0	670.5	73179	3.5	.0	2G4	4.54	.02	5.40	8.89	52.10			2	29	32	26.51		.02			
670.5	671.5	73180	1.0	.0	2E46	4.78	.40	3.25	7.08	31.49			2	29	32	7.25		.02			
671.5	676.0	73181	4.5	.0	2E1	4.11	.14	1.34	1.89	10.30			2	29	32	.27		.02			
676.0	680.0	73182	4.0	.0	2E4	4.44	.02	1.16	2.91	13.69			2	29	32	.04		.02			
680.0	683.0	73183	3.0	.0	2E0	4.54	.02	1.89	2.00	17.10			3	22	25	.04		.05			
683.0	684.0	73184	1.0	.0	2C0	4.66	.02	2.64	1.10	20.60			3	22	25	.04		.05			
684.0	686.0	73185	2.0	.0	2D0	3.10	.11	.62	7.28	12.30			3	22	25	.22		.05			
686.0	689.5	73186	3.5	.0	2D4	3.43	.13	2.58	9.32	13.69			3	22	25	.26		.05			
689.5	690.5	73187	1.0	.0	2D4	4.30	.16	2.64	4.38	6.90			3	22	25	.05		.05			
690.5	696.0	73188	5.5	.0	2E19	3.79	.26	.27	.55	4.09			3	22	25	.04		.05			
696.0	701.0	73189	5.0	.0	2E19	3.97	.20	.83	2.72	15.09			3	22	25	.08		.05			
701.0	706.0	73190	5.0	.0	2C3	3.85	.11	.23	.94				3	28	31	.07		.05			
706.0	711.0	73191	5.0	.0	2E19	4.15	.41	.11	.96				3	28	31	.05		.05			
711.0	716.0	73192	5.0	.0	2E19	4.02	.56	.11	.85	9.19			3	28	31	.04		.05			
716.0	721.0	73193	5.0	.0	2E19	4.08	.65	.26	.29	4.79			3	28	31	.08		.05			
721.0	726.0	73194	5.0	.0	2E19	4.06	.59	.46	.73	3.39			7	26	33	.02		.23			
726.0	727.0	73195	1.0	.0	2E19	3.43	.26	.38	1.19	9.59			7	26	33	.29		.23			
727.0	731.0	73196	4.0	.0	2F4	4.67	.17	8.32	12.40	6.50			7	26	33	.27		.23			
731.0	734.0	73197	3.0	.0	2F48	4.50	.13	8.30	12.00	44.60			7	26	33	.14		.23			
734.0	736.0	73198	2.0	.0	2E89	4.26	.26	.86	1.82	9.90			7	26	33	.02		.23			
736.0	741.0	73199	5.0	.0	2E89	4.09	.20	.72	1.89	8.59			7	26	33	.04		.23			
741.0	746.0	73200	5.0	.0	2E19	3.72	.35	.53	1.35	8.19			5	26	31	.05		.10			
746.0	751.0	73201	5.0	.0	2E81	3.97	.26	.17	.81	7.49			5	26	31	.04		.10			
751.0	756.0	73202	5.0	.0	2E81	4.08	.42	.05	.66				5	26	31	.02		.10			
756.0	761.0	73203	5.0	.0	2E81	3.93	.35	.11	.65	4.79			5	26	31	.04		.10			
761.0	766.0	73204	5.0	.0	2E91	3.91	.34	.02	1.17				4	26	31	.04		.08			

DDH: 76-03 UTM-N: 8798.3 UTM-E: 15009.1 UTM-ELEV: 4166.0 TOTAL DEPTH: 866.0 SECTION: 123+015
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

-----DEPTHS----						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
766.0	771.0	73205	5.0	.0	2E19	3.79	.32	.17	1.08					4	26	31	.08		.08		
771.0	776.0	73206	5.0	.0	2E19	4.06	.38	.11	.88					4	26	31	.02		.08		
776.0	781.0	73207	5.0	.0	2E19	3.83	.34	.51	1.89	7.49				4	26	31	.05		.08		
781.0	784.0	73208	3.0	.0	2F4	4.42	.04	10.27	20.80	23.30				6	10	16	.08		.05		
784.0	786.1	73209	2.1	.0	2E0	4.42	.13	.10	1.65					6	10	16	.04		.05		
786.1	788.0	73210	1.9	.0	2F4	4.21	.07	5.12	14.80	27.10				6	10	16	.02		.05		
788.0	791.0	73211	3.0	.0	0Q9	2.93	.17	3.04	1.87	28.80				6	10	16	.05		.05		
791.0	796.0	73212	5.0	.0	2B0	2.85	.08	.56	1.78					6	10	16	.27		.05		
796.0	798.0	73213	2.0	.0	2B0	2.87	.11	.47	.90	10.30				6	10	16	.32		.05		
798.0	801.4	73214	3.4	.0	2B9	3.14	.20	.84	3.00	6.59				6	10	16	.13		.05		
801.4	805.0	73215	3.6	.0	2C7&	3.12	.05	.28	1.58	6.59				4	13	18	.14		.04		
805.0	806.0	73216	1.0	.0	2D4	3.75	.08	5.28	13.40	33.89				4	13	18	.07		.04		
806.0	811.0	73217	5.0	.0	2D0	3.35	.08	2.27	5.79	20.89				4	13	18	.08		.04		
811.0	816.0	73218	5.0	.0	2D4	3.70	.11	7.04	17.00	40.50				4	13	18	.10		.04		
816.0	821.0	73219	5.0	.0	2D0	3.49	.07	2.48	6.65	20.89				4	13	18	.11		.04		
821.0	822.3	73220	1.3	.0	2D0	3.35	.22	2.37	6.28	31.89				4	13	18	.11		.04		
822.3	826.0	73221	3.7	.0	2D0	3.02	.13	2.41	2.54	23.00				4	4	9	.20		.05		
826.0	831.0	73222	5.0	.0	2C0	2.98	.19	.49	.99	9.90				4	4	9	.24		.05		
831.0	836.0	73223	5.0	.0	2B0	2.98	.17	.40	2.50	10.59				4	4	9	.23		.05		
836.0	841.5	73224	5.5	.0	2B0	2.87	.10	.66	1.69	12.69				4	4	9	.27		.05		

DDH: 76-04 UTM-N: 8676.0 UTM-E: 15107.6 UTM-ELEV: 4156.9 TOTAL DEPTH: 890.0 SECTION: 124
 RFE: S2 RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
628.7	632.0	73230	3.3	.0	2F64	3.89	.34	6.91	6.76	98.00		.14	5	25	30	.16		.16			
632.0	637.0	73231	5.0	.0	2F64	4.41	.17	5.67	5.50	70.29		.14	5	25	30	15.51		.16			
637.0	642.0	73232	5.0	.0	2E4	4.25	.02	3.08	4.95	36.00		.07	5	25	30	9.69		.16			
642.0	647.0	73233	5.0	.0	2E0	4.38	.11	1.28	2.52	2.70		.07	5	25	30	.02		.16			
647.0	652.0	73234	5.0	.0	2E0	3.79	.10	.67	.67	15.09			1	27	29	.02					
652.0	657.0	73235	5.0	.0	2E0	3.99	.04	.08	.26	3.39			1	27	29	.02					
657.0	662.0	73236	5.0	.0	2EC	3.68	.02	.11	.20				1	27	29	.02					
662.0	667.0	73237	5.0	.0	2EC	3.72	.02	.20	.17	11.59			1	27	29	.01					
667.0	672.0	73238	5.0	.0	2EC	3.89	.02	.24	.20				2	28	30	.02		.02			
672.0	677.0	73239	5.0	.0	2EC	3.72	.04	.17	.08				2	28	30	.01		.02			
677.0	682.0	73240	5.0	.0	2EC	3.45	.04	.28	.11	13.00			2	28	30	.02		.02			
682.0	687.0	73241	5.0	.0	2E0	4.51	.05	2.08	2.99	15.09		.01	2	28	30	.02		.02			
687.0	692.0	73242	5.0	.0	2E0	3.85	.05	1.27	.23	45.89		1.99	3	31	35	.01		.02			
692.0	697.0	73243	5.0	.0	2E4	5.34	.07	3.89	1.30	15.40		.07	3	31	35	.01		.02			
697.0	702.0	73244	5.0	.0	2E4	4.48	.24	2.81	2.73	14.40		.01	3	31	35	.02		.02			
702.0	707.0	73245	5.0	.0	2E0	4.33	.10	.80	1.35	7.49			3	31	35	.02		.02			
707.0	712.0	73246	5.0	.0	2E0	4.71	.07	.13	.11	7.90			3	32	35	.10		.02			
712.0	717.0	73247	5.0	.0	2G0	4.74	.07	4.37	8.75	39.79		.14	3	32	35	25.50		.02			
717.0	722.0	73248	5.0	.0	2H0	4.37	.44	2.37	3.62	21.89		.14	3	32	35	1.32		.02			
722.0	727.0	73249	5.0	.0	2EC	4.15	.04	.28	.26	8.90			3	32	35	.11		.02			
727.0	732.0	73250	5.0	.0	2EC	4.06	.05	1.50	2.10	4.09		.07	4	27	31	.02		.08			
732.0	737.0	73251	5.0	.0	2EC4	4.02	.14	3.39	4.02	28.80		.07	4	27	31	.08		.08			
737.0	742.0	73252	5.0	.0	2EC	3.70	.23	.69	1.33			.07	4	27	31	.13		.08			
742.0	747.0	73253	5.0	.0	2EC	3.83	.53	.19	.68	4.79			4	27	31	.02		.08			
747.0	752.0	73254	5.0	.0	1D4	3.31	.27	2.06	2.12	16.39		.21	6	14	21	.02		.17			
752.0	757.0	73255	5.0	.0	2EC	3.74	.23	1.03	1.44	8.19		.14	6	25	31	.02		.17			
757.0	762.0	73256	5.0	.0	2EC	4.08	.26	.57	1.76	6.50			6	25	31	.05		.17			
762.0	767.0	73257	5.0	.0	2E8	4.51	.45	.57	1.11	6.50			6	25	31	.02		.17			
767.0	772.0	73258	5.0	.0	2EF	4.15	.44	2.41	2.72	12.30		.07	4	27	32	.10		.08			
772.0	777.0	73259	5.0	.0	2F4	4.50	.08	4.95	10.19	18.80		.07	4	27	32	.02		.08			
777.0	782.0	73260	5.0	.0	2E1	4.09	.19	1.88	2.27	6.20		.07	4	27	32	.05		.08			
782.0	787.0	73261	5.0	.0	2E14	3.97	.05	2.75	5.41	18.80		.14	4	27	32	.05		.08			
787.0	792.0	73262	5.0	.0	2D0	3.29	.08	2.73	6.95	35.70		1.37	4	12	17	.05		.05			
792.0	797.0	73263	5.0	.0	2C0	3.37	.05	.49	1.69	19.89		.62	4	12	17	.05		.05			
797.0	802.0	73264	5.0	.0	2D4	3.62	.04	6.20	13.19	44.60		.21	4	12	17	.07		.05			
802.0	807.0	73265	5.0	.0	2D4	3.74	.08	6.90	16.39	56.89		.27	4	12	17	.11		.05			
807.0	812.0	73266	5.0	.0	2C0	2.89	.07	1.36	1.66	32.90		.55	4	3	8	.20		.08			
812.0	817.0	73267	5.0	.0	2D0	3.22	.17	3.00	4.70	53.79		1.92	4	3	8	.28		.08			

DDH: 76-05 UTM-N: 8584.0 UTM-E: 14797.0 UTM-ELEV: 4100.2 TOTAL DEPTH: 744.0 SECTION: 123+015
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	---ASSAYS---														
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
486.0	488.0	73272	2.0	.0	1E19	2.91	.05	.06	.07	3.40				5	4	10	.40				.06
488.0	490.0	73273	2.0	.0	2C9	3.08	.52	.17	.07	112.40				5	4	10	.11				.06
490.0	492.4	73274	2.4	.0	2L14	2.90	.18	.30	.15	7.50				4	4	9	.69				.07
492.4	493.9	73275	1.5	.0	1E19	2.77	.09	.06	.08	4.10				4	4	9	.45				.07
493.9	495.0	73276	1.1	.0	2B9	2.96	.35	.17	.12					4	4	9	5.08				.07
495.0	500.0	73277	5.0	.0	2B9C	3.02	.29	2.52	1.68	49.70				4	4	9	.97				.07
500.0	505.0	73278	5.0	.0	2B0C	2.99	.12	.13	.05					4	4	9	2.36				.07
505.0	510.0	73279	5.0	.0	2B0	2.79	.10	.11	.14					4	4	9	1.63				.07
510.0	515.0	73280	5.0	.0	2C9C	3.27	.21	.22	.80	7.20				8	16	24	.35				.14
515.0	517.5	73281	2.5	.0	2C9	3.08	.26	.45	.23	2.40				8	16	24	1.50				.14
517.5	520.0	73282	2.5	.0	2D4	3.86	.03	8.32	16.80	108.00				8	16	24	.45				.14
520.0	524.0	73283	4.0	.0	2G4	4.57	.05	4.47	6.90	46.30				8	16	24	25.76				.14
524.0	525.0	73284	1.0	.0	2E43	4.11	.34	4.18	8.75	59.00				8	16	24	.03				.14
525.0	530.0	73285	5.0	.0	2E43	4.13	.27	5.44	8.22	59.70				8	16	24	.06				.14
530.0	535.0	73286	5.0	.0	2H49	3.80	.30	4.83	5.35	61.00				19	12	32	9.99				.08
535.0	539.7	73287	4.7	.0	2H49	4.22	.35	6.34	3.84	61.50				19	12	32	.07				.08
539.7	544.4	73288	4.7	.0	2C39	3.48	.29	.66	1.91	20.60				19	12	32	.79				.08
544.4	546.4	73289	2.0	.0	2G4	4.08	.06	5.18	5.66	78.90				19	12	32	16.86				.08
563.0	564.0	73291	1.0	.0	1D41	2.83	.03	.10	.16	6.90				2	2	5	2.44				.05
564.0	565.3	73292	1.3	.0	1E19	2.86	.04	.18	.40	6.00				1	1	3	2.67				.05
565.3	570.0	73293	4.7	.0	1D4C	2.90	.05	.27	.64	5.50				2	2	5	3.17				.05
570.0	572.2	73294	2.2	.0	1E19	2.92	.03	.89	1.06	27.80				11	10	22	2.19				.15
572.2	575.0	73295	2.8	.0	1D4C	2.99	.06	1.69	1.88	32.60				11	10	22	4.61				.15
575.0	577.2	73296	2.2	.0	1D4	2.91	.04	.54	.90					11	10	22	2.37				.15
577.2	580.0	73297	2.8	.0	2K49	4.15	.33	5.37	7.55	56.90				11	10	22	.08				.15
580.0	585.0	73298	5.0	.0	2K79	4.09	.25	3.17	3.07	68.60				11	10	22	1.50				.15
585.0	588.0	73299	3.0	.0	2H9&	3.61	.36	2.18	2.10	46.60				11	10	22	.78				.15
588.0	590.0	73300	2.0	.0	1H4*	2.88	.08	.16	.27					11	10	22	.19				.15
590.0	595.7	73301	5.7	.0	1H4*	2.92	.08	2.78	1.58	46.60				14	9	24	.45				.14
595.7	600.0	73302	4.3	.0	2H39	4.55	.38	3.33	2.76	31.20				14	9	24	.06				.14
600.0	605.0	73303	5.0	.0	2Q9C	3.28	.27	3.07	1.01	60.30				14	9	24	.12				.14
605.0	610.0	73304	5.0	.0	2C9C	3.11	.33	.67	.26	30.20				14	9	24	.09				.14
610.0	612.0	73305	2.0	.0	2C9C	3.58	.23	.89	.55	28.80				7	29	36	.04				.22
612.0	614.4	73306	2.4	.0	1H4*	3.01	.10	4.65	.46	30.90				7	29	36	.16				.22
614.4	615.9	73307	1.5	.0	2E39	3.88	.29	1.59	.35	42.50				7	29	36	.05				.22
615.9	620.0	73308	4.1	.0	2E9&	4.89	.24	1.33	.84	17.10				7	29	36	.07				.22
620.0	625.0	73309	5.0	.0	2E9&	4.99	.27	2.27	1.49	18.50				7	29	36	.05				.22
625.0	626.0	73310	1.0	.0	2E9&	4.83	.31	1.60	.92	11.60				7	29	36	.05				.22
626.0	630.5	73311	4.5	.0	2F49	4.64	.26	8.90	9.43	99.40				7	29	36	.05				.22
630.5	635.0	73312	4.5	.0	2E49	4.80	.20	4.99	3.61	55.50				4	33	38	.05				.09
635.0	637.0	73313	2.0	.0	2E4C	4.70	.19	5.05	2.24	24.00				4	33	38	.04				.09
637.0	640.0	73314	3.0	.0	2E9	4.90	.39	1.89	1.04	20.60				4	33	38	.09				.09
640.0	642.0	73315	2.0	.0	2E9	4.70	.37	1.24	2.06	16.40				4	33	38	.31				.09
642.0	646.0	73316	4.0	.0	2E9&	3.91	.24	.49	.61	13.00				4	33	38	.04				.09
646.0	650.0	73317	4.0	.0	2F4C	4.96	.08	5.09	6.64	42.50				4	33	38	.05				.09
650.0	655.0	73318	5.0	.0	2F49	4.81	.21	4.85	8.58	39.80				5	35	40	.03				.17
655.0	660.0	73319	5.0	.0	2E0C	4.92	.07	1.88	5.76	3.40				5	35	40	.04				.17
660.0	665.0	73320	5.0	.0	2E0C	4.48	.37	2.83	3.98	32.60				5	35	40	.04				.17
665.0	670.0	73321	5.0	.0	2F49	4.76	.26	2.47	3.23	26.70				5	35	40	.06				.17
670.0	675.0	73322	5.0	.0	2E49	4.56	.27	1.64	2.36	15.10				6	26	32	.13				.12

DDH: 76-05 UTM-N: 8584.0 UTM-E: 14797.0 UTM-ELEV: 4100.2 TOTAL DEPTH: 744.0 SECTION: 123+015
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

-----DEPTHS-----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
675.0	678.2	73323	3.2	.0	2E48	4.72	.26	2.88	3.70	12.30				6 26	32	.04		.12			
678.2	680.0	73324	1.8	.0	2C0	3.07	.13	.30	.53					6 26	32	.19		.12			
680.0	683.0	73325	3.0	.0	2C9	3.53	.25	2.54	1.50	8.20				6 26	32	.13		.12			
683.0	685.0	73326	2.0	.0	2E11	4.78	.13	3.64	6.66	25.40				6 26	32	.05		.12			
685.0	688.0	73327	3.0	.0	2E11	4.45	.15	3.45	5.84	20.60				6 26	32	.04		.12			
688.0	690.0	73328	2.0	.0	2F4	4.80	.06	6.86	12.50	13.00				6 26	32	.05		.12			
690.0	695.0	73329	5.0	.0	2F4	4.79	.05	4.63	8.83	29.50				6 26	32	.03		.12			
695.0	699.5	73330	4.5	.0	2E41	4.29	.16	2.37	5.28	19.20				5 25	31	.07		.04			
699.5	700.5	73331	1.0	.0	2D5	3.30	.14	3.00	5.37	52.80				5 25	31	.21		.04			
700.5	705.0	73332	4.5	.0	2E41	4.65	.15	4.25	5.81	3.40				5 25	31	.04		.04			
705.0	709.0	73333	4.0	.0	2D0&	3.26	.11	1.62	3.32	19.50				5 25	31	.21		.04			
709.0	710.0	73334	1.0	.0	2E13	4.76	.06	.10	.61	13.70				5 25	31	.03		.04			
710.0	712.5	73335	2.5	.0	2E13	4.01	.14	.44	1.00	13.70				5 25	31	.07		.04			
712.5	715.0	73336	2.5	.0	2D9	3.03	.24	1.98	3.83	13.00				6 5	11	.15		.07			
715.0	720.0	73337	5.0	.0	2C01	3.47	.12	1.65	2.27	19.20				6 5	11	.17		.07			
720.0	725.3	73338	5.3	.0	2B0	2.99	.15	.28	.23	47.30				6 5	11	.15		.07			

DDH: 76-06 UTM-N: 8805.2 UTM-E: 14600.1 UTM-ELEV: 4058.7 TOTAL DEPTH: 801.0 SECTION: 121+000
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

-----DEPTHS-----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
489.4	492.3	73344	2.9	.0	2C9	3.04	.24	.20	.24	5.80			2	11	13	.37					.09
492.3	493.4	73345	1.1	.0	2A13	3.15	.28	.23	.30	12.00			2	11	13	.08					.09
493.4	498.4	73346	5.0	.0	2C9	3.27	.41	.34	.32	27.40			2	11	13	.11					.09
498.4	500.9	73347	2.5	.0	2C9	3.13	.33	.42	.61	17.50			2	11	13	.07					.09
500.9	502.0	73348	1.1	.0	2A4L	3.37	.12	2.40	6.75	30.50			2	11	13	.44					.09
502.0	506.0	73349	4.0	.0	2D49	3.52	.23	6.45	11.20	63.10			2	11	13	.19					.09
506.0	507.0	73350	1.0	.0	2F4&	4.68	.10	9.82	8.35	139.60			2	11	13	2.44					.09
507.0	512.0	73351	5.0	.0	2G4	4.58	.17	8.41	6.45	102.50			2	15	17	26.39					.38
512.0	517.0	73352	5.0	.0	2G4	4.65	.15	7.13	6.62	95.00			2	15	17	26.12					.38
517.0	522.0	73353	5.0	.0	2G4	4.61	.16	6.22	6.15	82.60			2	15	17	28.10					.38
522.0	527.0	73354	5.0	.0	2G4	4.63	.09	6.39	6.54	86.10			2	15	17	29.39					.38
527.0	532.0	73355	5.0	.0	2G4	4.85	.11	8.00	6.70	114.50			9	10	20	28.69					.32
532.0	537.0	73356	5.0	.0	2G4	4.69	.11	7.38	7.22	102.50			9	10	20	32.27					.32
537.0	541.6	73357	4.6	.0	2G4	4.65	.10	6.93	7.08	94.30			9	10	20	27.83					.32
541.6	544.5	73358	2.9	.0	2H41	3.89	.15	4.59	5.62	64.50			9	10	20	4.89					.32
544.5	545.8	73359	1.3	.0	2G9L	3.50	.63	1.86	.54	38.70			9	10	20	15.21					.32
545.8	546.7	73360	.9	.0	2H16	3.62	.16	3.19	1.53	47.00			9	10	20	9.81					.32
546.7	549.4	73361	2.7	.0	2G1	3.19	.15	.75	.80	14.70			9	10	20	18.14					.32
549.4	554.4	73362	5.0	.0	2G1	3.15	.07	.72	1.10	10.60			9	10	20	29.46					.32
554.4	559.4	73363	5.0	.0	2C6	2.99	.05	1.66	2.22	30.50			9	10	20	7.49					.32
559.4	564.4	73364	5.0	.0	2C6	2.99	.03	1.27	1.29	21.90			9	10	20	6.08					.32
564.4	566.3	73365	1.9	.0	2D0&	3.12	.06	2.42	5.93	39.10			9	10	20	.88					.32
566.3	571.3	73366	5.0	.0	2A41	3.00	.07	1.95	2.22	28.50			9	10	20	.81					.32
571.3	576.3	73367	5.0	.0	2D5	2.92	.10	2.51	6.37	33.30			12	14	27	.15					.11
576.3	578.4	73368	2.1	.0	2H43	4.41	.24	7.61	12.30	87.80			12	14	27	.09					.11
578.4	579.5	73369	1.1	.0	2F49	4.39	.23	5.15	7.98	68.20			12	14	27	.07					.11
579.5	580.4	73370	.9	.0	2H49	4.18	.20	4.61	5.56	48.30			12	14	27	.13					.11
580.4	581.0	73371	.6	.0	2E49	4.55	.38	5.20	4.80	78.50			12	14	27	.06					.11
581.0	581.5	73372	.5	.0	2H43	4.18	.20	4.61	5.56	48.30			12	14	27	.13					.11
581.5	584.5	73373	3.0	.0	2F46	4.50	.21	6.28	9.25	78.20			12	14	27	8.52					.11
584.5	585.0	73374	.5	.0	2F49	4.59	.46	6.52	9.75	85.40			12	14	27	.23					.11
585.0	586.0	73375	1.0	.0	2E49	4.27	.40	3.38	3.60	44.90			12	14	27	.55					.11
586.0	588.0	73376	2.0	.0	2H69	4.37	.29	3.60	1.56	58.30			12	14	27	14.32					.11
588.0	593.0	73377	5.0	.0	2G9	4.59	2.30	1.88	.70	72.70			17	15	32	9.09					.11
593.0	597.0	73378	4.0	.0	2G49	4.72	.20	2.55	1.56	32.60			3	32	36	13.14					.08
597.0	599.7	73379	2.7	.0	2G4	4.98	.10	5.15	5.85	47.30			3	32	36	33.36					.08
599.7	600.2	73380	.5	.0	2E5	4.85	.16	1.70	.90	15.80			3	32	36	1.20					.08
600.2	603.0	73381	2.8	.0	2E49	4.72	.22	1.66	3.13	21.90			3	32	36	.14					.08
603.0	604.0	73382	1.0	.0	2E4	4.48	.09	3.39	5.48	36.30			3	32	36	.77					.08
604.0	604.5	73383	.5	.0	2E46	4.76	.11	2.44	1.80	27.80			3	32	36	8.41					.08
604.5	609.7	73384	5.2	.0	2E0	4.81	.11	1.00	.46	14.70			3	32	36	2.82					.08
609.7	612.5	73385	2.8	.0	2G4	4.78	.05	4.29	6.65	38.10			4	26	31	24.74					.13
612.5	614.5	73386	2.0	.0	2E46	4.83	.06	2.69	4.52	25.70			4	26	31	1.12					.13
614.5	619.0	73387	4.5	.0	2E46	4.74	.16	4.28	5.10	49.00			4	26	31	6.48					.13
619.0	620.0	73388	1.0	.0	2E4	4.72	.09	3.38	6.48	40.10			4	26	31	.09					.13
620.0	623.0	73389	3.0	.0	2E1	3.70	.11	.82	.56	29.80			4	26	31	.69					.13
623.0	624.8	73390	1.8	.0	2G4	4.90	.07	5.34	8.26	48.70			4	26	31	35.00					.13
624.8	625.1	73391	.3	.0	2E1	3.41	.07	.11	.27	9.20			4	26	31	.06					.13
625.1	625.6	73392	.5	.0	2E1	4.20	.16	.59	.61	17.80			4	26	31	.06					.13
625.6	626.1	73393	.5	.0	2E43	4.69	.22	5.02	6.28	35.70			4	26	31	.05					.13
626.1	628.0	73394	1.9	.0	2E43	4.50	.25	2.88	3.60	23.30			4	26	31	.67					.13

DDH: 76-06 UTM-N: 8805.2 UTM-E: 14600.1 UTM-ELEV: 4058.7 TOTAL DEPTH: 801.0 SECTION: 121+000
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

-----DEPTHS-----						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
628.0	630.1	73395	2.1	.0	2E43	4.65	.38	2.65	4.82	26.40			5	22	28	.04		.16			
630.1	633.4	73396	3.3	.0	2F47	4.24	.81	3.62	8.20	34.30			5	22	28	.13		.16			
633.4	638.4	73397	5.0	.0	2D9	3.03	.34	.85	4.46	17.50			5	22	28	.41		.16			
638.4	640.3	73398	1.9	.0	2D0	3.13	.13	.67	3.38	18.80			5	22	28	.22		.16			
640.3	641.0	73399	.7	.0	2E4	4.74	.11	2.12	5.46	20.90			5	22	28	.04		.16			
641.0	643.3	73400	2.3	.0	2E49	4.31	.21	2.08	3.90	16.50			5	22	28	.03		.16			
643.3	645.2	73401	1.9	.0	2E49	4.27	.25	2.30	4.18	13.00			5	22	28	.03		.16			
645.2	650.7	73402	5.5	.0	2E89	4.24	.52	1.44	2.51	14.70			5	22	28	.05		.16			
650.7	656.0	73403	5.3	.0	2E89	4.50	.36	1.37	1.64	13.70			4	37	41	.14		.11			
656.0	660.0	73404	4.0	.0	2E19	4.02	.41	1.19	1.09	15.80			4	37	41	.03		.11			
660.0	660.8	73405	.8	.0	2E8	4.55	.15	.30	.40	9.90			4	37	41	.04		.11			
660.8	661.4	73406	.6	.0	2E0	4.61	.10	1.31	2.42	14.70			4	37	41	.05		.11			
661.4	662.2	73407	.8	.0	2E9	4.67	.21	.53	.81	14.70			4	37	41	.11		.11			
662.2	662.5	73408	.3	.0	2E4	4.50	.17	1.64	3.21	14.40			4	37	41	.03		.11			
662.5	667.5	73409	5.0	.0	2E89	4.42	.36	.30	.78	13.40			4	37	41	.04		.11			
667.5	671.3	73410	3.8	.0	2E9	4.55	.39	.30	1.30	14.40			6	28	34	.11		.11			
671.3	675.9	73411	4.6	.0	2F1	4.29	.21	2.00	4.40	17.50			6	28	34	.06		.11			
675.9	677.0	73412	1.1	.0	2F1	3.48	.36	5.00	3.44	40.80			6	28	34	.19		.11			
677.0	678.0	73413	1.0	.0	2E4&	4.67	.19	1.85	3.80	18.20			6	28	34	.05		.11			
678.0	680.5	73414	2.5	.0	2E4	4.44	.05	4.33	4.33	27.80			6	28	34	.07		.11			
680.5	681.0	73415	.5	.0	2E1	4.72	.04	.87	.87	13.70			6	28	34	.06		.11			
681.0	682.0	73416	1.0	.0	2E1	4.27	.06	1.21	1.21	14.40			6	28	34	.03		.11			
682.0	685.2	73417	3.2	.0	2E1	5.81	.08	1.75	1.75	20.20			6	28	34	.09		.11			
685.2	689.1	73418	3.9	.0	2H43	3.48	.41	4.00	7.83	29.10			6	28	34	.04		.11			
689.1	692.0	73419	2.9	.0	2D39	2.91	.81	.61	3.95	85.40			7	7	14	.18		.05			
692.0	696.0	73420	4.0	.0	2A4	3.11	.17	1.78	4.60	30.20			7	7	14	.15		.05			
696.0	700.0	73421	4.0	.0	2A4	3.04	.34	3.40	3.72	54.20			7	7	14	.19		.05			
700.0	704.5	73422	4.5	.0	2A0	2.96	.17	1.30	2.42	27.80			7	7	14	.25		.05			
704.5	705.7	73423	1.2	.0	2A0	2.88	.05	1.72	2.03	38.10			7	7	14	.17		.05			
705.7	707.7	73424	2.0	.0	2A0	2.75	.05	.79	2.70	17.10			7	7	14	.18		.05			
707.7	712.7	73425	5.0	.0	2A4	2.75	.04	1.12	3.92	30.50			3	7	10	.15		.03			
712.7	717.7	73426	5.0	.0	2A4	2.62	.09	.90	3.20	34.30			3	7	10	.16		.03			
717.7	719.7	73427	2.0	.0	2A0	2.76	.14	.18	.15	14.70			3	7	10	.18		.03			
719.7	723.2	73428	3.5	.0	2A0	2.54	.11	.13	.18	15.80			3	7	10	.19		.03			
723.2	723.7	73429	.5	.0	2A0	3.44	.23	.14	.30	20.20			3	7	10	.09		.03			
723.7	727.0	73430	3.3	.0	2A0	2.42	.05	.95	1.61	63.80			3	7	10	.28		.03			
727.0	727.9	73431	.9	.0	0Q9	2.72	.30	1.02	.37	93.60			5	8	14	.05		.02			
727.9	730.0	73432	2.1	.0	2B4	2.92	.13	4.35	3.60	154.30			5	8	14	.04		.02			
730.0	731.8	73433	1.8	.0	2D5	2.92	.13	4.35	3.60	154.30			5	8	14	.05		.02			
731.8	736.8	73434	5.0	.0	2D5	2.86	.15	1.68	5.55	44.60			5	8	14	.20		.02			
736.8	741.8	73435	5.0	.0	2D5	2.88	.15	2.24	2.90	175.20			5	8	14	.15		.02			
741.8	746.8	73436	5.0	.0	2D5	3.03	.12	2.81	4.74	50.10			5	8	14	.23		.02			
746.8	750.5	73437	3.7	.0	2D79	3.22	.42	1.64	4.43	26.40			5	8	14	.14		.02			
750.5	755.0	73438	4.5	.0	2D79	3.07	.27	2.00	6.45	32.90			8	3	11	.13		.04			
755.0	756.3	73439	1.3	.0	2D5	2.99	.13	4.80	8.91	48.00			8	3	11	.16		.04			
756.3	761.3	73440	5.0	.0	2A41	2.72	.06	3.30	4.50	55.20			8	3	11	.22		.04			
761.3	766.3	73441	5.0	.0	2A4	3.22	.12	1.60	4.45	35.70			8	3	11	.15		.04			
766.3	771.3	73442	5.0	.0	2A0	2.46	.11	.33	1.90	8.20			8	3	11	.16		.04			

DDH: 76-07 UTM-N: 8614.0 UTM-E: 14406.4 UTM-ELEV: 4051.3 TOTAL DEPTH: 787.0 SECTION: 121+000
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	---ASSAYS---														
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
516.3	518.5	73448	2.2	.0	2D4	3.13	.12	5.85	10.40	45.60			4	12	17	.14		.09			
518.5	520.5	73449	2.0	.0	2C0	3.06	.17	.65	2.95	12.70			4	12	17	.14		.09			
520.5	521.6	73450	1.1	.0	2E4	4.50	.06	2.89	6.00	35.30			4	12	17	.17		.09			
521.6	525.0	73451	3.4	.0	2G4	4.59	.13	6.60	6.55	86.70			8	21	29	12.46		.29			
525.0	530.0	73452	5.0	.0	2E46	4.61	.24	7.16	6.10	102.20			8	21	29	5.80		.29			
530.0	535.0	73453	5.0	.0	2E46	4.63	.19	6.48	6.36	109.70			8	21	29	3.93		.29			
535.0	539.0	73454	4.0	.0	2E43	4.10	.23	6.24	7.02	91.90			8	21	29	1.48		.29			
539.0	540.3	73455	1.3	.0	1D4	2.79	.20	1.06	.39	30.50			8	21	29	1.41		.29			
540.3	542.0	73456	1.7	.0	2J4	3.60	.10	5.85	20.60	88.80			8	21	29	.53		.29			
542.0	545.0	73457	3.0	.0	2J4	3.60	.10	5.85	20.60	88.80			8	21	29	.53		.29			
545.0	549.2	73458	4.2	.0	2H43	4.27	.43	5.70	7.37	77.10			23	12	35	.13		.20			
549.2	550.2	73459	1.0	.0	2H43	4.00	.30	5.16	5.23	60.70			23	12	35	.17		.20			
550.2	553.9	73460	3.7	.0	2H39	4.02	.29	4.37	5.00	51.40			23	12	35	.15		.20			
553.9	555.0	73461	1.1	.0	2H39	3.75	.26	2.43	5.00	29.50			23	12	35	.15		.20			
555.0	559.9	73462	4.9	.0	2H39	4.20	.33	3.77	5.70	47.70			23	12	35	.15		.20			
559.9	560.7	73463	.8	.0	2H39	4.10	.33	3.86	5.91	44.90			23	12	35	.16		.20			
560.7	562.5	73464	1.8	.0	2E43	3.24	.13	3.41	6.23	39.80			23	12	35	.18		.20			
562.5	565.0	73465	2.5	.0	2D0	2.87	.06	.83	3.39	15.80			9	28	37	.13		.10			
565.0	565.8	73466	.8	.0	2D4	3.62	.16	4.75	20.60	75.10			9	28	37	.17		.10			
565.8	566.6	73467	.8	.0	2D43	4.20	.43	4.70	7.68	41.50			9	28	37	.15		.10			
566.6	568.1	73468	1.5	.0	2H43	4.17	.34	6.81	12.00	87.80			9	28	37	.17		.10			
568.1	571.0	73469	2.9	.0	2E49	4.37	.76	3.30	4.33	36.70			9	28	37	.13		.10			
571.0	573.5	73470	2.5	.0	2H39	4.12	.69	1.79	.84	27.40			9	28	37	.14		.10			
573.5	575.5	73471	2.0	.0	2E8	4.29	.17	1.96	.94	23.00			9	28	37	.15		.10			
575.5	580.5	73472	5.0	.0	2E9	4.46	.30	.37	.47	6.50			9	28	37	.15		.10			
580.5	583.6	73473	3.1	.0	2E9	4.69	.62	.30	1.01	12.70			9	28	37	.13		.10			
583.6	585.0	73474	1.4	.0	2F4	4.57	.12	6.85	9.15	52.50			4	26	30	.15		.06			
585.0	590.0	73475	5.0	.0	2F4	4.55	.14	7.19	8.50	53.10			4	26	30	.16		.06			
590.0	592.0	73476	2.0	.0	2E49	4.65	.24	3.24	1.98	28.10			4	26	30	.10		.06			
592.0	596.0	73477	4.0	.0	2E9	4.74	.39	.92	.98	15.80			4	26	30	.14		.06			
596.0	596.5	73478	.5	.0	2D9	4.46	.27	4.76	5.00	49.40			4	26	30	.19		.06			
596.5	597.0	73479	.5	.0	0Q9	3.82	.63	3.56	5.41	78.20			4	26	30	.20		.06			
597.0	602.0	73480	5.0	.0	2B0	2.85	.08	1.00	2.10	20.90			4	26	30	.13		.06			
602.0	607.0	73481	5.0	.0	2B0	2.81	.13	.68	1.31	16.80			3	22	26	.18		.05			
607.0	612.0	73482	5.0	.0	2B49	3.01	.30	1.35	4.90	37.70			3	22	26	.21		.05			
612.0	615.5	73483	3.5	.0	2E4	4.67	.02	5.20	4.90	48.00			3	22	26	.14		.05			
615.5	620.5	73484	5.0	.0	2E4	4.44	.03	4.02	5.70	39.40			3	22	26	.16		.05			
620.5	625.5	73485	5.0	.0	2E49	4.83	.57	4.72	5.72	52.10			3	22	26	.17		.05			
625.5	630.5	73486	5.0	.0	2E4	4.63	.12	3.77	6.80	35.30			7	28	35	.15		.05			
630.5	631.4	73487	.9	.0	2E4	4.22	.07	4.08	6.98	49.40			7	28	35	.16		.05			
631.4	636.4	73488	5.0	.0	2E49	4.72	.22	3.91	6.89	43.90			7	28	35	.15		.05			
636.4	640.0	73489	3.6	.0	2H43	3.97	.52	4.51	7.06	41.80			7	28	35	.14		.05			
640.0	641.0	73490	1.0	.0	2E4	4.02	.17	1.03	4.54	13.40			7	28	35	.16		.05			
641.0	643.0	73491	2.0	.0	1D4	3.11	.23	.85	1.55	52.10			7	28	35	.15		.05			
643.0	646.0	73492	3.0	.0	2B49	3.02	.20	2.20	3.80	41.10			5	4	9	.24		.04			
646.0	651.0	73493	5.0	.0	2B4	3.17	.16	4.47	3.85	91.20			5	4	9	.14		.04			
651.0	656.0	73494	5.0	.0	2B4	3.01	.09	4.18	3.23	95.30			5	4	9	.31		.04			
656.0	661.0	73495	5.0	.0	2B0	2.79	.07	.49	1.57	19.90			5	4	9	.28		.04			
661.0	666.0	73496	5.0	.0	2B4	3.16	.06	5.93	1.79	128.20			6	6	12	.23		.04			
666.0	669.3	73497	3.3	.0	2A0	2.79	.06	1.16	2.22	23.70			3	1	5	.21		.06			
669.3	670.0	73498	.7	.0	1D4	2.79	.08	.50	.29	12.70			3	1	5	.17		.06			

DDH: 76-07 UTM-N: 8614.0 UTM-E: 14406.4 UTM-ELEV: 4051.3 TOTAL DEPTH: 787.0 SECTION: 121+000
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

-----DEPTHS----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
670.0	675.0	73499	5.0	.0	1D4	2.79	.03	.05	.08				3	1	5	.25		.06			
675.0	680.0	73500	5.0	.0	1D4	2.72	.02	.07	.14				3	1	5	.18		.06			
680.0	685.0	73501	5.0	.0	1D4	2.72	.01	.09	.12	8.90			3	1	5	.18		.06			
685.0	685.6	73502	.6	.0	2A4	2.77	.03	1.83	3.40	31.90			3	1	5	.15		.06			
685.6	686.2	73503	.6	.0	1D4	2.67	.04	.09	.59	3.10			3	1	5	.30		.06			
686.2	688.2	73504	2.0	.0	2A4	2.83	.04	1.64	2.82	22.30			3	1	5	.20		.06			
688.2	690.5	73505	2.3	.0	1D4	2.76	.10	.45	.36	22.30			3	1	5	.88		.06			
690.5	691.9	73506	1.4	.0	2A0	2.87	.08	.97	2.77	31.90			3	1	5	.15		.06			

DDH: 76-08 UTM-N: 8395.3 UTM-E: 14621.1 UTM-ELEV: 4041.9 TOTAL DEPTH: 690.0 SECTION: 123+015
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

-----DEPTHS----						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
455.1	459.7	73514	4.6	.0	2D43	4.24	.42	6.46	9.63	80.90				16	18	34	.08		.31		
459.7	461.8	73515	2.1	.0	2H43	4.22	.66	2.18	3.75	32.20				16	18	34	.06		.31		
461.8	464.9	73516	3.1	.0	2H43	4.37	.52	6.52	5.95	68.60				16	18	34	.09		.31		
464.9	470.0	73517	5.1	.0	2F46	4.33	.19	7.95	6.16	35.70				16	18	34	5.76		.31		
470.0	475.0	73518	5.0	.0	2G47	4.67	.18	7.58	6.16	109.00				9	13	22	21.10		.48		
475.0	480.0	73519	5.0	.0	2G47	4.61	.12	7.85	5.95	108.30				9	13	22	21.40		.48		
480.0	483.0	73520	3.0	.0	2G47	4.72	.11	7.10	5.77	102.90				9	13	22	11.47		.48		
483.0	486.8	73521	3.8	.0	2H46	4.55	.36	7.40	5.78	110.40				9	13	22	13.28		.48		
486.8	487.6	73522	.8	.0	2H46	4.17	.39	7.45	7.74	114.50				9	13	22	9.58		.48		
487.6	492.7	73523	5.1	.0	2B0&	3.94	.08	.82	.82	9.60				9	13	22	4.42		.48		
492.7	493.2	73524	.5	.0	2J47	4.44	.06	25.20	22.80	350.40				7	3	11	1.19		.16		
493.2	496.2	73525	3.0	.0	2B0	3.26	.07	.83	2.18	5.80				7	3	11	21.45		.16		
496.2	498.6	73526	2.4	.0	2B4	3.18	.07	2.10	2.84	38.40				7	3	11	12.44		.16		
498.6	503.5	73527	4.9	.0	2B0	2.93	.05	.96	1.12	19.50				7	3	11	4.58		.16		
503.5	504.1	73528	.6	.0	0Q9[	3.64	.19	9.82	4.75	146.80				7	3	11	1.24		.16		
504.1	509.1	73529	5.0	.0	0Q9[	3.72	.16	5.15	5.60	91.90				7	3	11	7.04		.16		
509.1	509.5	73530	.4	.0	2A4	3.08	.05	2.28	5.04	37.70				7	3	11	1.19		.16		
509.5	512.0	73531	2.5	.0	2A4	3.03	.05	2.52	4.28	21.90				7	3	11	.47		.16		
512.0	515.0	73532	3.0	.0	2A4	2.95	.04	1.68	4.32	33.60				9	1	11	.60		.07		
515.0	520.0	73533	5.0	.0	2A4	2.90	.05	1.52	4.60	33.60				9	1	11	.56		.07		
520.0	521.0	73534	1.0	.0	2A4	3.33	.19	5.14	4.71	118.00				9	1	11	.07		.07		
521.0	525.0	73535	4.0	.0	2H43	4.22	.24	7.01	9.82	128.40				9	1	11	.08		.07		
525.0	526.0	73536	1.0	.0	2A4[	2.90	.18	.98	2.09	38.40				9	1	11	.56		.07		
526.0	527.0	73537	1.0	.0	2A4[	2.80	.03	1.31	4.20	41.10				9	1	11	.76		.07		
527.0	528.0	73538	1.0	.0	2A4[	2.88	.06	1.48	3.40	27.80				9	1	11	.51		.07		
528.0	529.6	73539	1.6	.0	2A4[	2.58	.02	1.56	2.68	39.40				9	1	11	.83		.07		
529.6	530.4	73540	.8	.0	2A0[	2.91	.05	.10	.15	1.70				9	1	11	.63		.07		
530.4	533.3	73541	2.9	.0	2A0	2.98	.04	.44	.78	8.20				9	1	11	.58		.07		
533.3	536.3	73542	3.0	.0	2A0	2.78	.05	.37	.44	7.50				7	4	11	.58		.09		
536.3	541.3	73543	5.0	.0	2A0	2.99	.08	.74	1.15	18.20				7	4	11	.58		.09		
541.3	545.2	73544	3.9	.0	2D0[	3.11	.11	1.60	3.12	41.80				7	4	11	.31		.09		
545.2	548.0	73545	2.8	.0	2H43	4.07	.30	6.17	11.04	94.60				7	4	11	.34		.09		
548.0	549.5	73546	1.5	.0	2A4	2.99	.05	1.71	4.20	23.30				7	4	11	.33		.09		
549.5	553.0	73547	3.5	.0	2B4[	2.98	.06	3.24	4.35	39.10				7	4	11	.30		.09		
553.0	558.0	73548	5.0	.0	2B0&	2.99	.10	1.13	2.77	17.10				5	2	8	.26		.06		
558.0	563.0	73549	5.0	.0	2B0&	2.87	.02	.85	2.02	10.60				5	2	8	.78		.06		
563.0	565.2	73550	2.2	.0	0Q9	3.03	.11	2.85	4.45	31.50				5	2	8	.05		.06		
565.2	565.8	73551	.6	.0	2D49	4.10	.52	9.65	12.60	138.50				5	2	8	.08		.06		
565.8	570.8	73552	5.0	.0	2D0[	3.01	.11	2.57	5.10	45.30				5	2	8	.07		.06		
570.8	572.5	73553	1.7	.0	2D4[	3.22	.14	3.29	8.27	45.30				5	2	8	.07		.06		
572.5	573.5	73554	1.0	.0	2D4[	4.18	.32	7.76	10.66	103.90				13	25	39	.05		.13		
573.5	576.4	73555	2.9	.0	2H43	4.39	.38	2.51	3.20	25.40				13	25	39	.05		.13		
576.4	578.7	73556	2.3	.0	2E9	4.57	.30	1.56	1.20	15.10				13	25	39	.04		.13		
578.7	580.0	73557	1.3	.0	2F4	4.83	.11	6.60	6.10	29.80				13	25	39	.04		.13		
580.0	583.0	73558	3.0	.0	2D3	4.33	.48	4.33	3.94	63.80				13	25	39	.08		.13		
583.0	584.0	73559	1.0	.0	2E4	4.76	.10	1.66	5.83	2.70				13	25	39	.04		.13		
584.0	588.4	73560	4.4	.0	2E0	4.74	.11	2.10	1.16	15.10				13	25	39	.04		.13		
588.4	594.0	73561	5.6	.0	2F4	4.90	.06	6.31	10.54	41.10				13	25	39	.07		.13		
594.0	599.0	73562	5.0	.0	2E0	4.78	.24	1.30	2.57	14.40				17	23	41	.03		.10		
599.0	602.0	73563	3.0	.0	2E4	4.63	.30	2.98	4.20	16.40				17	23	41	.04		.10		
602.0	604.0	73564	2.0	.0	2F4	4.72	.16	5.09	7.12	28.80				17	23	41	.03		.10		

DDH: 76-08 UTM-N: 8395.3 UTM-E: 14621.1 UTM-ELEV: 4041.9 TOTAL DEPTH: 690.0 SECTION: 123+015
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

-----DEPTHS-----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
604.0	607.0	73565	3.0	.0	2E49	4.76	.20	3.59	6.20	1.40			17	23	41	.04		.10			
607.0	609.7	73566	2.7	.0	2H43	4.10	.66	4.48	4.34	45.30			17	23	41	.03		.10			
609.7	614.7	73567	5.0	.0	2H43	3.88	.61	5.04	5.92	47.30			17	23	41	.07		.10			
614.7	619.7	73568	5.0	.0	2H43	3.68	1.02	3.56	3.71	25.40			25	11	37	.03		.09			
619.7	624.7	73569	5.0	.0	2H43	4.29	.62	4.48	5.90	56.90			25	11	37	.04		.09			
624.7	629.7	73570	5.0	.0	2H43	3.76	.71	2.18	4.96	53.50			25	11	37	.13		.09			
629.7	632.7	73571	3.0	.0	2D43	3.53	.58	4.97	10.80	66.50			25	11	37	.07		.09			
632.7	635.2	73572	2.5	.0	2D37	3.33	.33	1.10	4.25	24.00			2	3	6	.17		.04			
635.2	640.0	73573	4.8	.0	2A0	3.09	.14	.90	2.39	24.70			2	3	6	.19		.04			
640.0	645.0	73574	5.0	.0	2A0	2.59	.04	.93	2.25	25.40			2	3	6	.18		.04			
645.0	650.0	73575	5.0	.0	2A0	2.91	.04	1.35	2.29	17.80			2	3	6	.15		.04			
650.0	655.0	73576	5.0	.0	2A4	2.97	.07	2.00	3.98	31.50			2	3	6	.16		.04			

DDH: 76-09 UTM-N: 8199.0 UTM-E: 14420.5 UTM-ELEV: 4012.5 TOTAL DEPTH: 638.0 SECTION: 123+015
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

-----DEPTHS-----		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
496.2	500.0	73581	3.8	.0	1D49	3.38	.26	3.16	2.80	47.00			20	9	30	.21		.21			
500.0	500.7	73582	.7	.0	2H43	4.22	1.36	6.53	6.18	133.00			20	9	30	.06		.21			
500.7	504.0	73583	3.3	.0	2H43	4.50	.80	4.54	4.82	49.40			20	9	30	.03		.21			
504.0	506.5	73584	2.5	.0	2E49	4.81	.26	4.32	6.06	47.30			7	24	32	.03		.20			
506.5	508.0	73585	1.5	.0	2E41	4.88	.15	4.18	3.77	30.90			7	24	32	.05		.20			
508.0	511.0	73586	3.0	.0	0Q9	3.94	.30	5.68	5.23	61.70			7	24	32	.13		.20			
511.0	514.0	73587	3.0	.0	2E41	3.89	.25	3.54	6.35	49.40			7	24	32	.07		.20			
514.0	518.4	73588	4.4	.0	2E49	4.74	.20	5.04	5.80	41.10			7	24	32	.11		.20			
518.4	519.7	73589	1.3	.0	2E41	4.22	.43	5.02	4.68	66.50			7	24	32	.10		.20			
519.7	520.3	73590	.6	.0	2E41	4.10	.17	5.44	9.58	75.40			7	24	32	.22		.20			
520.3	521.3	73591	1.0	.0	2E46	4.63	.31	4.68	5.38	64.40			7	24	32	5.18		.20			
521.3	522.5	73592	1.2	.0	2E46	4.65	.18	5.09	6.20	65.10			7	24	32	6.91		.20			
522.5	522.8	73593	.3	.0	2E46	4.35	.49	4.00	5.00	54.90			7	24	32	.16		.20			
522.8	524.1	73594	1.3	.0	2E46	4.72	.09	7.55	8.86	236.60			7	24	32	.09		.20			
524.1	525.9	73595	1.8	.0	2E46	4.57	.15	4.67	5.01	61.70			9	24	34	7.70		.36			
525.9	527.2	73596	1.3	.0	2E46	4.55	.28	5.35	5.40	76.80			9	24	34	1.46		.36			
527.2	528.5	73597	1.3	.0	2E46	4.59	.24	5.02	6.00	84.30			9	24	34	.87		.36			
528.5	530.7	73598	2.2	.0	2E41	4.61	.24	5.48	5.68	68.60			9	24	34	5.59		.36			
530.7	535.7	73599	5.0	.0	2E41	4.63	.28	5.00	5.39	73.40			9	24	34	4.47		.36			
535.7	540.7	73600	5.0	.0	2E41	4.57	.17	6.10	5.80	93.90			9	24	34	3.81		.36			
540.7	542.7	73601	2.0	.0	2H43	3.97	.24	5.43	6.66	98.70			9	24	34	.66		.36			
542.7	545.0	73602	2.3	.0	2D4	3.17	.13	2.62	7.86	35.30			7	2	9	.15		.08			
545.0	550.0	73603	5.0	.0	2D0	3.13	.17	1.36	3.44	33.30			7	2	9	.22		.08			
550.0	551.5	73604	1.5	.0	2D9	3.23	.22	2.18	6.58	15.80			7	2	9	.33		.08			
551.5	553.2	73605	1.7	.0	2B4	3.00	.14	1.68	3.00	52.50			7	2	9	.31		.08			
553.2	556.5	73606	3.3	.0	2A9	2.94	.22	1.10	1.86	18.50			7	2	9	.35		.08			
556.5	561.5	73607	5.0	.0	2A0	2.75	.06	.45	1.28	13.40			7	2	9	.42		.08			
561.5	566.5	73608	5.0	.0	2A0	2.65	.05	.48	.94	20.90			4	1	5	.46		.03			
566.5	571.5	73609	5.0	.0	2A0	2.74	.05	.55	.96	5.80			4	1	5	.50		.03			
571.5	571.9	73610	.4	.0	1D09	2.71	.13	.53	1.33	27.80			4	1	5	.49		.03			
571.9	573.0	73611	1.1	.0	1D09	2.79	.08	.16	.25	31.90			4	1	5	.86		.03			
573.0	574.3	73612	1.3	.0	2A9	2.72	.99	.59	.82	20.60			4	1	5	.37		.03			
574.3	575.6	73613	1.3	.0	2A0	2.70	.07	.52	.97	17.80			4	1	5	.38		.03			
575.6	577.1	73614	1.5	.0	2A0	2.67	.05	1.16	1.13	39.80			4	1	5	.36		.03			
577.1	580.5	73615	3.4	.0	2A0	2.67	.05	1.26	1.40	43.20			4	1	5	.40		.03			
580.5	585.5	73616	5.0	.0	2B0	2.79	.05	1.15	1.16	39.40			4	1	5	.39		.03			
585.5	589.0	73617	3.5	.0	2A0	2.81	.09	3.08	.91	105.60			3	3	7	.35		.03			
589.0	593.8	73618	4.8	.0	2B0	2.81	.08	2.52	1.22	86.40			3	3	7	.38		.03			
593.8	596.4	73619	2.6	.0	2A0	2.76	.04	.80	.93	27.40			3	3	7	.31		.03			
596.4	601.4	73620	5.0	.0	2A0	2.62	.07	.60	1.09	20.60			3	3	7	.33		.03			

05MAR87 !THE IMPERIAL ANVIL!

ASSAY LISTING (DEPTH SEQUENCE) DH015

PAGE:123

DDH: 76-10 UTM-N: 8397.2 UTM-E: 14213.9 UTM-ELEV: 4009.1 TOTAL DEPTH: 626.0 SECTION: 121+000
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

-----DEPTHS-----						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
521.5	524.2	73626	2.7	.0	2C0&	3.34	.14	.40	.95	2.10				7 18	26	.06		.05			
524.2	529.2	73627	5.0	.0	2D0(	3.04	.11	1.50	3.40	18.50				7 18	26	.18		.05			
529.2	530.5	73628	1.3	.0	2H43	4.57	.27	6.63	9.25	94.60				7 18	26	.37		.05			
530.5	531.3	73629	.8	.0	2H43	4.29	.36	3.80	5.88	23.30				7 18	26	.05		.05			
531.3	534.0	73630	2.7	.0	2H43	4.59	.21	8.50	12.40	36.00				7 18	26	.06		.05			
534.0	537.0	73631	3.0	.0	2H43	4.50	.06	5.34	8.25	34.30				7 18	26	.07		.05			
537.0	538.0	73632	1.0	.0	2D4	4.46	.10	4.54	7.65	42.50				3 4	7	.11		.04			
538.0	542.0	73633	4.0	.0	2C0	2.97	.18	.80	2.50	18.50				3 4	7	.27		.04			
542.0	545.0	73634	3.0	.0	2C0	2.84	.14	1.08	1.37	53.40				3 4	7	.24		.04			
545.0	550.0	73635	5.0	.0	2A0	2.91	.08	.91	1.89	24.70				3 4	7	.22		.04			
550.0	555.0	73636	5.0	.0	2A4	2.91	.04	1.97	4.42	21.20				3 4	7	.36		.04			
555.0	560.0	73637	5.0	.0	2A0	2.92	.06	.85	.95	10.30				3 4	7	.37		.04			

DDH: 76-11 UTM-N: 8618.1 UTM-E: 13987.0 UTM-ELEV: 3992.0 TOTAL DEPTH: 595.0 SECTION: 119+000
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

-----DEPTHS-----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
501.0	506.0	73643	5.0	.0	2B45	3.09	.05	3.48	5.48	38.70			4	8	13	.37		.07			
506.0	511.0	73644	5.0	.0	009	2.92	.03	2.28	5.33	30.50			4	8	13	.23		.07			
511.0	516.0	73645	5.0	.0	2B45	2.96	.05	1.80	3.85	26.40			4	8	13	.32		.07			
516.0	521.0	73646	5.0	.0	2E42	4.62	.12	4.90	7.90	56.90			4	8	13	.11		.07			
521.0	526.0	73647	5.0	.0	2E42	3.73	.17	4.60	6.58	65.80			7	8	15	.06		.18			
526.0	531.0	73648	5.0	.0	009	2.90	.03	5.33	2.20	90.90			7	8	15	.16		.18			
531.0	536.0	73649	5.0	.0	2J41	3.76	.25	11.90	13.50	310.00			7	8	15	.29		.18			
536.0	541.0	73650	5.0	.0	2J41	4.00	.27	12.30	16.60	384.00			7	8	15	.17		.18			
541.0	544.0	73651	3.0	.0	2J4	3.26	.11	6.85	8.88	132.40			7	8	15	.24		.18			

DDH: 76-12 UTM-N: 8993.3 UTM-E: 14806.6 UTM-ELEV: 4069.0 TOTAL DEPTH: 787.0 SECTION: 121+000
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

---DEPTHS---		-----ASSAYS-----																			
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	Ba0 %	Hg %	Mn %	As %	Ba %	S.G. W.R.
535.8	536.2	73656	.4	.0	2E4	4.27	.06	5.10	6.22	107.00			4	30	34	.02		.19			
536.2	536.9	73657	.7	.0	1F4	2.87	.18	.90	.33	19.90			4	30	34	.02		.19			
536.9	542.5	73658	5.6	.0	2E4	4.56	.17	5.36	3.50	109.70			4	30	34	.02		.19			
542.5	547.5	73659	5.0	.0	2C0	4.04	.03	.20	.13	7.20			1	32	34	.02		.16			
547.5	552.6	73660	5.1	.0	2C0	3.76	.03	.81	.76	11.60			1	32	34	.02		.16			
552.6	556.0	73661	3.4	.0	2E49	4.68	.27	2.24	2.27	27.40			1	32	34	.02		.16			
556.0	561.0	73662	5.0	.0	2C0	3.95	.09	1.08	.21	16.10			1	32	34	.02		.16			
561.0	566.0	73663	5.0	.0	2C0	4.04	.02	.20	.11	6.50			1	37	38	.01		.04			
566.0	566.7	73664	.7	.0	2E0	4.38	.08	.45	.25	9.20			1	37	38	.03		.04			
566.7	568.2	73665	1.5	.0	2C0	4.32	.08	.61	.20	10.60			1	37	38	.03		.04			
568.2	576.0	73666	7.8	.0	2E0	4.32	.07	.61	.45	15.80			1	37	38	.03		.04			
576.0	581.2	73667	5.2	.0	2E41	4.73	.10	2.85	3.52	27.40			1	37	38	2.51		.04			
581.2	586.4	73668	5.2	.0	2E46	4.82	.03	2.05	4.50	18.80			2	36	38	8.28		.09			
586.4	590.1	73669	3.7	.0	2E41	4.55	.33	2.40	3.18	29.50			2	36	38	2.81		.09			
590.1	591.0	73670	.9	.0	2E48	4.50	.38	4.44	3.33	54.20			2	36	38	.08		.09			
591.0	593.2	73671	2.2	.0	2C9	4.46	.27	.77	.32	21.60			2	36	38	.07		.09			
593.2	593.7	73672	.5	.0	2F0	4.86	.16	3.26	3.60	39.10			2	36	38	.06		.09			
593.7	595.0	73673	1.3	.0	2C0	4.60	.08	.74	.61	13.70			2	36	38	.01		.09			
595.0	599.2	73674	4.2	.0	2C0	4.16	.09	.54	.44	56.20			2	36	38	.01		.09			
599.2	600.0	73675	.8	.0	2F9	4.64	.24	5.42	3.79	16.10			2	36	38	.02		.09			
600.0	600.7	73676	.7	.0	2C0	4.85	.06	.92	.46	12.00			2	36	38	.01		.09			
600.7	601.6	73677	.9	.0	2E9	4.54	.28	1.95	1.93	26.40			2	36	38	.02		.09			
601.6	602.4	73678	.8	.0	2E89	4.24	.30	1.37	1.96	25.70			2	36	38	.02		.09			
602.4	606.7	73679	4.3	.0	2E49	4.23	.34	1.38	2.90	21.60			4	28	33	.01		.20			
606.7	610.0	73680	3.3	.0	2E9	4.41	.24	1.27	1.68	17.10			4	28	33	.02		.20			
610.0	613.0	73681	3.0	.0	2E49	4.92	.24	4.25	1.13	29.80			4	28	33	.02		.20			
613.0	619.0	73682	6.0	.0	2D0	3.67	.10	1.31	3.61	16.80			4	28	33	.08		.20			
619.0	623.0	73683	4.0	.0	2D0	3.72	.06	.90	6.35	20.20			4	28	33	.05		.20			
623.0	626.0	73684	3.0	.0	2D0	3.21	.14	1.63	5.21	31.50			3	27	31	.07		.27			
626.0	627.0	73685	1.0	.0	2D0	3.31	.12	.83	6.37	31.50			3	27	31	.05		.27			
627.0	631.0	73686	4.0	.0	2D35	3.71	.07	1.57	6.95	28.80			3	27	31	.10		.27			
631.0	632.4	73687	1.4	.0	2E0	4.71	.03	2.46	1.04	21.20			3	27	31	.03		.27			
632.4	634.6	73688	2.2	.0	2C9	4.58	.22	.74	.80	19.90			3	27	31	.03		.27			
634.6	635.8	73689	1.2	.0	2E48	4.20	.31	4.84	2.66	40.80			3	27	31	.12		.27			
635.8	638.0	73690	2.2	.0	2C9	4.40	.42	.90	.82	19.20			3	27	31	.02		.27			
638.0	641.7	73691	3.7	.0	2C9	4.24	.28	1.04	2.14	20.90			3	27	31	.01		.27			
641.7	644.3	73692	2.6	.0	2E89	4.19	.35	1.19	1.76	19.50			3	27	31	.02		.27			
644.3	645.3	73693	1.0	.0	2E9	4.20	.33	.56	1.19	15.10			9	29	38	.02		.41			
645.3	648.0	73694	2.7	.0	2E48	4.39	.22	2.60	2.70	21.90			9	29	38	.02		.41			
648.0	651.1	73695	3.1	.0	2E89	4.26	.33	1.24	2.55	19.50			9	29	38	.01		.41			
651.1	654.5	73696	3.4	.0	2E39	4.62	.28	.90	1.77	10.30			9	29	38	.02		.41			
654.5	655.0	73697	.5	.0	2E9	3.18	.22	.72	1.30	13.00			9	29	38	.14		.41			
655.0	657.0	73698	2.0	.0	2E39	4.22	.31	.37	.88	9.90			9	29	38	.01		.41			
657.0	658.2	73699	1.2	.0	1D41	3.70	.65	.92	1.41	20.90			9	29	38	.05		.41			
658.2	660.0	73700	1.8	.0	2C9	4.20	.37	.19	.72	18.50			9	29	38	.03		.41			
660.0	664.0	73701	4.0	.0	2C9	5.04	.41	.90	1.80	9.60			9	29	38	.01		.41			
664.0	665.0	73702	1.0	.0	2F4	5.10	.06	3.50	8.52	11.60			4	30	34	.02		.19			
665.0	670.0	73703	5.0	.0	2E89	4.09	.23	1.36	2.15	8.20			4	30	34	.01		.19			
670.0	672.0	73704	2.0	.0	2E8	4.47	.17	.73	1.90	8.20			4	30	34	.10		.19			
672.0	675.0	73705	3.0	.0	2F4	4.71	.12	4.19	9.60	18.50			4	30	34	.02		.19			
675.0	677.0	73706	2.0	.0	2E4	4.42	.06	1.33	5.87	8.90			4	30	34	.03		.19			

DDH: 76-12 UTM-N: 8993.3 UTM-E: 14806.6 UTM-ELEV: 4069.0 TOTAL DEPTH: 787.0 SECTION: 121+000
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

-----DEPTHS-----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
677.0	681.8	73707	4.8	.0	2F4	4.50	.09	5.90	14.40	20.20			4	30	34	.02		.19			
681.8	682.4	73708	.6	.0	2F4	4.06	.05	2.82	8.43	12.30			4	30	34	.01		.19			
682.4	684.0	73709	1.6	.0	2F4	4.41	.13	6.76	10.10	19.20			4	30	34	.02		.19			
684.0	685.7	73710	1.7	.0	2F4	4.54	.28	7.53	11.40	22.60			4	24	28	.04		.29			
685.7	690.0	73711	4.3	.0	2E48	3.77	.54	1.27	3.20	12.70			4	24	28	.01		.29			
690.0	692.5	73712	2.5	.0	2F4	4.36	.15	4.66	8.15	21.90			4	24	28	.01		.29			
692.5	694.6	73713	2.1	.0	2H42	3.96	.13	4.38	8.57	55.20			4	24	28	.02		.29			
694.6	696.9	73714	2.3	.0	2F4	4.64	.02	6.50	12.80	51.40			4	24	28	.05		.29			
696.9	702.0	73715	5.1	.0	2E41	3.76	.07	1.45	3.43	22.60			4	24	28	.04		.29			
702.0	707.0	73716	5.0	.0	2E1	3.68	.16	.51	2.45	9.60			4	24	28	.03		.29			
707.0	712.0	73717	5.0	.0	2E41	3.76	.17	3.50	1.25	96.30			2	18	20	.03		.15			
712.0	717.0	73718	5.0	.0	2E41	3.46	.07	2.08	3.02	25.40			2	18	20	.03		.15			
717.0	722.0	73719	5.0	.0	2E41	3.59	.05	2.49	5.12	21.90			2	18	20	.04		.15			
722.0	727.0	73720	5.0	.0	2A4	3.64	.05	2.30	7.55	26.70			2	18	20	.05		.15			
727.0	732.0	73721	5.0	.0	2A4	3.43	.06	4.63	10.90	31.90			2	13	15	.04		.14			
732.0	737.0	73722	5.0	.0	2A4	3.22	.09	3.10	7.25	24.30			2	13	15	.05		.14			
737.0	739.8	73723	2.8	.0	2A4	3.32	.05	1.02	3.18	14.10			2	13	15	.06		.14			
739.8	744.8	73724	5.0	.0	2A4	3.49	.09	1.55	6.21	17.80			2	13	15	.05		.14			
744.8	749.8	73725	5.0	.0	2A4	3.43	.05	3.97	11.40	25.40			3	6	10	.10		.13			
749.8	754.8	73726	5.0	.0	2A4	3.33	.05	6.45	15.00	38.40			3	6	10	.10		.13			
754.8	755.7	73727	.9	.0	2E41	3.96	.13	8.35	18.50	47.70			3	6	10	.04		.13			
755.7	756.3	73728	.6	.0	2B43	3.62	.16	8.55	8.95	66.20			3	6	10	.05		.13			
756.3	758.0	73729	1.7	.0	2D08	2.95	.07	2.82	2.77	68.20			3	6	10	.10		.13			

DDH: 76-13 UTM-N: 9003.1 UTM-E: 14399.2 UTM-ELEV: 4002.2 TOTAL DEPTH: 714.0 SECTION: 119+000
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

-----DEPTHS-----						-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
481.5	486.5	73735	5.0	.0	2E01	3.25	.17	.18	1.29	17.20			3	13	17	.05				.03
486.5	490.3	73736	3.8	.0	2C0	3.04	.20	.62	3.05	32.20			3	13	17	.07				.03
490.3	494.2	73737	3.9	.0	2D05	3.28	.05	1.00	7.48	22.60			3	13	17	.08				.03
494.2	499.2	73738	5.0	.0	2G42	4.65	.17	5.80	5.91	85.40			6	23	29	12.87				.30
499.2	504.2	73739	5.0	.0	2G42	4.63	.12	4.97	5.82	73.00			6	23	29	13.74				.30
504.2	509.2	73740	5.0	.0	2G42	4.55	.11	5.22	5.32	84.00			6	23	29	22.42				.30
509.2	514.0	73741	4.8	.0	2G42	4.37	.34	4.40	4.90	80.20			6	23	29	7.30				.30
514.0	519.0	73742	5.0	.0	2E48	4.42	.08	3.07	2.71	57.30			5	11	16	.33				.24
519.0	524.0	73743	5.0	.0	2D07	3.38	.22	3.62	4.16	69.60			5	11	16	5.24				.24
524.0	529.0	73744	5.0	.0	2A4	2.92	.04	2.27	4.53	47.70			5	11	16	.37				.24
529.0	534.0	73745	5.0	.0	2A4	2.90	.04	1.30	3.98	36.30			5	11	16	.44				.24
534.0	539.0	73746	5.0	.0	2A4	2.85	.04	1.79	3.78	43.60			5	5	11	.98				.13
539.0	544.0	73747	5.0	.0	2A4	2.79	.03	1.21	2.92	35.30			5	5	11	.61				.13
544.0	549.0	73748	5.0	.0	2A4	3.11	.10	1.94	5.54	47.30			5	5	11	.88				.13
549.0	554.0	73749	5.0	.0	2G4	4.08	.28	7.63	5.87	147.40			5	5	11	10.53				.13
554.0	559.0	73750	5.0	.0	2G42	4.57	.17	5.51	7.20	112.10			6	21	27	28.32				.10
559.0	564.0	73751	5.0	.0	2F46	4.42	.12	5.49	8.80	90.50			6	21	27	5.55				.10
564.0	569.0	73752	5.0	.0	2G4	4.57	.08	5.86	7.70	75.10			6	21	27	26.56				.10
569.0	574.0	73753	5.0	.0	2F4	4.78	.05	6.78	11.70	63.80			6	21	27	.49				.10
574.0	579.0	73754	5.0	.0	2F0	4.31	.23	3.00	3.90	31.20			5	34	40	.37				.17
579.0	584.0	73755	5.0	.0	2E8	4.50	.18	1.60	2.57	20.20			5	34	40	.07				.17
584.0	589.0	73756	5.0	.0	2E8	4.10	.26	1.78	2.46	17.10			5	34	40	.06				.17
589.0	594.0	73757	5.0	.0	2E8	4.52	.19	1.81	4.00	14.40			5	34	40	.05				.17
594.0	599.0	73758	5.0	.0	2E8	4.60	.59	1.73	2.86	23.00			4	35	39	.07				.08
599.0	604.0	73759	5.0	.0	2F0	4.72	.22	5.08	4.30	24.00			4	35	39	.04				.08
604.0	609.0	73760	5.0	.0	2F0	4.86	.31	2.68	4.53	21.60			4	35	39	.37				.08
609.0	614.0	73761	5.0	.0	2F0	4.50	.15	3.88	5.89	30.20			4	35	39	.09				.08
614.0	619.0	73762	5.0	.0	2F0	4.75	.13	3.85	5.52	29.80			5	27	32	.06				.03
619.0	624.0	73763	5.0	.0	2F0	4.81	.08	3.95	5.39	23.70			5	27	32	.06				.03
624.0	629.0	73764	5.0	.0	2F0	4.70	.11	3.46	6.25	28.80			5	27	32	.10				.03
629.0	634.0	73765	5.0	.0	2A0	3.02	.08	.73	2.62	19.90			5	27	32	.18				.03
634.0	639.0	73766	5.0	.0	2A0	2.81	.05	1.18	1.81	36.70			2	4	6	.19				.02
639.0	644.0	73767	5.0	.0	2A0	2.85	.09	.88	2.29	25.70			2	4	6	.19				.02
644.0	649.0	73768	5.0	.0	2A4	2.81	.07	1.30	3.26	26.10			2	4	6	.24				.02
649.0	654.0	73769	5.0	.0	2A0	2.70	.04	.79	2.27	9.30			2	4	6	.20				.02
654.0	659.0	73770	5.0	.0	2A4	2.82	.03	1.30	3.28	18.20			3	1	5	.17				.03
659.0	660.5	73771	1.5	.0	2B4	3.00	.10	1.56	4.27	25.70			3	1	5	.09				.03

DDH: 76-14 UTM-N: 9203.0 UTM-E: 14598.0 UTM-ELEV: 4002.6 TOTAL DEPTH: 611.0 SECTION: 119+000
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

-----DEPTHS-----						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
444.0	449.0	73777	5.0	.0	2G48	4.09	.19	4.11	6.52	76.10			16	16	32	5.10		.22			
449.0	454.0	73778	5.0	.0	2H4	4.20	.17	5.00	7.90	85.70			16	16	32	6.17		.22			
454.0	459.0	73779	5.0	.0	2G4	3.67	.15	2.73	3.24	48.00			9	10	19	5.45		.22			
459.0	464.0	73780	5.0	.0	2L2	3.06	.12	1.08	1.02	15.10			9	10	19	4.71		.22			
464.0	469.0	73781	5.0	.0	2E46	3.90	.17	7.58	8.78	103.90			9	10	19	2.93		.22			
469.0	474.0	73782	5.0	.0	1D4	3.09	.52	1.68	1.95	49.40			9	10	19	2.54		.22			
474.0	479.0	73783	5.0	.0	1D4	2.96	.31	2.88	1.23	93.90			4	25	30	.35		.14			
479.0	484.0	73784	5.0	.0	2E0	4.20	.21	2.93	1.50	30.50			4	25	30	.08		.14			
484.0	489.0	73785	5.0	.0	2E4	4.47	.14	2.75	3.05	17.80			4	25	30	2.33		.14			
489.0	494.0	73786	5.0	.0	2F4	4.48	.21	4.38	5.85	34.30			4	25	30	.05		.14			
494.0	499.0	73787	5.0	.0	2E0	4.66	.44	1.60	1.54	32.90			15	23	39	.07		.27			
499.0	504.0	73788	5.0	.0	2E0	4.26	.27	1.51	1.57	24.30			15	23	39	.08		.27			
504.0	509.0	73789	5.0	.0	2E81	3.92	.22	1.77	1.30	21.90			15	23	39	.06		.27			
509.0	514.0	73790	5.0	.0	2E81	3.83	.16	2.02	1.40	24.70			15	23	39	.07		.27			
514.0	519.0	73791	5.0	.0	2E0	4.31	.17	2.10	2.00	22.60			7	31	38	.07		.23			
519.0	524.0	73792	5.0	.0	2E0	4.36	.19	2.38	2.37	18.80			7	31	38	.10		.23			
524.0	529.0	73793	5.0	.0	2E8	4.62	.26	2.10	2.42	20.90			7	31	38	.03		.23			
529.0	534.0	73794	5.0	.0	2E8	4.34	.27	4.12	4.84	38.10			7	31	38	.10		.23			
534.0	539.0	73795	5.0	.0	2E0	4.61	.21	3.13	2.51	24.30			3	35	39	.04		.09			
539.0	544.0	73796	5.0	.0	2E0	4.82	.36	1.05	3.46	10.60			3	35	39	.04		.09			
544.0	549.0	73797	5.0	.0	2F0	4.51	.20	3.26	5.20	11.60			3	35	39	.03		.09			
549.0	554.0	73798	5.0	.0	2F0	4.98	.16	1.49	4.96	11.60			3	35	39	.04		.09			
554.0	559.0	73799	5.0	.0	2F0	4.73	.16	2.90	4.83	17.80			4	30	34	.04		.05			
559.0	564.0	73800	5.0	.0	2E4&	4.58	.15	3.10	6.30	14.00			4	30	34	.28		.05			
564.0	569.0	73801	5.0	.0	2D5	3.60	.13	2.66	4.95	18.90			4	30	34	.04		.05			

DDH: 76-22 UTM-N: 8799.1 UTM-E: 14227.3 UTM-ELEV: 4012.1 TOTAL DEPTH: 630.0 SECTION: 119+000
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

-----DEPTHS-----						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
504.0	509.0	73807	5.0	.0	2B49	3.71	.22	3.80	3.50	31.90			5	14	19	.07		.11			
509.0	514.0	73808	5.0	.0	2F4	3.77	.13	4.30	5.80	37.00			5	14	19	.07		.11			
514.0	519.0	73809	5.0	.0	2E46	3.26	.35	2.60	4.30	26.10			5	14	19	7.09		.11			
519.0	524.0	73810	5.0	.0	2G42	3.80	.13	7.50	8.50	49.00			5	14	19	7.91		.11			
524.0	529.0	73811	5.0	.0	2F4	4.04	.04	7.00	8.30	41.10			4	31	35	.02		.06			
529.0	532.4	73812	3.4	.0	2F4	5.08	.31	4.80	6.11	33.20			4	31	35	.14		.06			
548.0	553.0	73814	5.0	.0	2H49	4.33	.53	7.00	9.30	58.30			28	12	40	.02		.06			
553.0	558.0	73815	5.0	.0	2H49	4.57	.61	4.90	6.50	40.50			28	12	40	.07		.06			
558.0	563.0	73816	5.0	.0	2H49	4.49	.32	7.60	8.40	58.60			28	12	40	.02		.06			
563.0	568.0	73817	5.0	.0	2F49	4.81	.36	5.30	7.50	42.50			3	33	37	.03		.04			
568.0	573.0	73818	5.0	.0	2F4	4.58	.10	6.70	8.30	54.90			3	33	37			.04			
573.0	578.0	73819	5.0	.0	2F4	4.69	.13	6.50	9.90	49.00			3	33	37	.01		.04			
578.0	583.0	73820	5.0	.0	2F4	4.76	.22	4.70	7.00	39.10			3	33	37	.01		.04			
583.0	588.0	73821	5.0	.0	2F4	4.84	.11	5.00	5.70	54.50			9	25	34	.04		.10			
588.0	593.0	73822	5.0	.0	2E48	4.70	.20	4.00	3.30	68.60			9	25	34	.14		.10			
593.0	598.0	73823	5.0	.0	2H49	4.54	.32	4.70	7.80	61.00			9	25	34	.11		.10			
598.0	603.0	73824	5.0	.0	2D0	3.43	.18	2.40	6.30	44.60			9	25	34	.10		.10			
603.0	608.0	73825	5.0	.0	2D0	2.89	.08	1.50	3.90	26.40			4	2	6	.15		.04			
608.0	613.0	73826	5.0	.0	2A4	2.71	.10	2.50	3.20	48.70			4	2	6	.15		.04			
613.0	618.0	73827	5.0	.0	1D21	2.74	.06	.08	.01	2.60			4	2	6	.21		.04			
618.0	622.0	73828	4.0	.0	1D21	2.73	.16	.02	.01	4.00			4	2	6	.22		.04			
622.0	626.0	73829	4.0	.0	1D21	2.44	.13	.03	.01	3.50			4	1	5	.18		.06			
626.0	630.0	73830	4.0	.0	1D21	2.75	.08	.03	.18	1.50			4	1	5	.14		.06			

DDH: 76916 UTM-N: 9168.9 UTM-E: 14246.5 UTM-ELEV: 3926.1 TOTAL DEPTH: 793.0 SECTION: 117+000
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
358.5	363.3	73850	4.8	.0	2H4	3.39	.33	5.02	5.96	62.10			7	23	31	.30		.17			
365.0	367.2	73852	2.2	.0	2H4	2.94	.10	.82	1.36	16.40			7	23	31	.09		.17			
367.2	371.0	73853	3.8	.0	2F4	5.13	.10	8.00	8.25	106.60			7	23	31	.10		.17			
371.0	371.9	73854	.9	.0	2G4	5.46	.10	5.58	6.44	77.50			7	23	31	7.59		.17			
371.9	376.5	73855	4.6	.0	2F4	5.75	.05	6.18	7.31	69.30			7	23	31	.06		.17			
376.5	378.7	73856	2.2	.0	2H4	3.89	.32	4.77	5.48	59.00			6	29	35	.15		.21			
378.7	380.4	73857	1.7	.0	2E4	6.17	.12	4.42	5.30	48.70			6	29	35	.04		.21			
380.4	381.4	73858	1.0	.0	2H4	4.69	.25	7.38	9.30	87.10			6	29	35	.04		.21			
381.4	389.5	73859	8.1	.0	2E4	4.31	.09	2.98	3.78	40.10			6	29	35	.02		.21			
389.5	392.6	73860	3.1	.0	2BE4	4.81	.08	4.66	5.40	51.40			6	29	35	1.34		.21			
392.6	396.0	73861	3.4	.0	2E4	4.49	.07	3.16	4.66	34.30			6	29	35	.14		.21			
396.0	400.3	73862	4.3	.0	2H4	4.17	.48	6.75	8.98	72.70			17	20	37	.20		.42			
400.3	401.6	73863	1.3	.0	2H4	3.86	.36	4.68	5.78	51.80			17	20	37	.10		.42			
401.6	403.0	73864	1.4	.0	2F4	5.92	.29	5.70	6.53	70.30			17	20	37	.04		.42			
403.0	408.0	73865	5.0	.0	2H4	3.94	.34	5.00	5.32	62.40			17	20	37	.06		.42			
408.0	413.0	73866	5.0	.0	2F8	5.99	.19	4.20	3.60	56.60			17	20	37	.20		.42			
413.0	418.0	73867	5.0	.0	2F8	4.52	.20	2.58	2.20	41.10			17	20	37	.04		.42			
418.0	422.0	73868	4.0	.0	2F8	4.65	.18	3.95	3.65	59.00			3	20	23	.20		.14			
422.0	423.9	73869	1.9	.0	1D4	3.02	.24	1.08	.98	25.70			3	20	23	1.17		.14			
423.9	425.2	73870	1.3	.0	2G48	4.27	.22	5.14	5.12	88.80			3	20	23	1.96		.14			
425.2	428.3	73871	3.1	.0	2F4	5.00	.09	5.85	5.70	76.80			3	20	23	.10		.14			
428.3	433.3	73872	5.0	.0	2G4	4.69	.09	6.35	7.75	66.50			3	20	23	31.74		.14			
433.3	435.0	73873	1.7	.0	2E4	4.61	.10	6.77	8.40	64.10			3	20	23	32.05		.14			
435.0	436.6	73874	1.6	.0	2G0	4.07	.25	3.60	3.12	38.40			3	20	23	.98		.14			
436.6	437.6	73875	1.0	.0	2E4	5.26	.09	3.09	3.92	30.20			5	35	41	9.51		.12			
437.6	443.0	73876	5.4	.0	2E0	4.57	.22	1.32	1.32	16.40			5	35	41	.02		.12			
443.0	447.6	73877	4.6	.0	2F0	4.55	.30	1.39	2.21	20.90			5	35	41	.04		.12			
447.6	449.0	73878	1.4	.0	2E34	4.15	1.08	2.11	2.35	39.10			5	35	41	.04		.12			
449.0	450.6	73879	1.6	.0	2E0	4.48	.79	1.06	1.26	21.60			5	35	41	.03		.12			
450.6	451.0	73880	.4	.0	2F4	4.55	.12	8.28	9.40	89.80			5	35	41	.14		.12			
451.0	456.0	73881	5.0	.0	2E4	4.59	.39	1.98	2.44	26.40			5	35	41	.03		.12			
456.0	460.0	73882	4.0	.0	2L9	2.93	.09	1.10	3.80	15.80			12	4	17	.11		.03			
460.0	463.0	73883	3.0	.0	2L9	2.63	.05	1.02	2.40	20.90			12	4	17	.11		.03			
463.0	466.3	73884	3.3	.0	2A4	3.46	.04	.77	3.71	27.80			12	4	17	.13		.03			
466.3	468.0	73885	1.7	.0	2E4	4.41	.03	4.00	6.65	38.40			12	4	17	.04		.03			
468.0	471.0	73886	3.0	.0	2A4	2.87	.15	1.21	3.94	58.30			12	4	17	.30		.03			
471.0	476.0	73887	5.0	.0	2H4	4.24	.44	4.21	6.45	42.90			12	4	17	.02		.03			
476.0	479.0	73888	3.0	.0	2H4	4.27	.41	4.02	5.20	41.10			7	3	11	.07		.02			
479.0	493.0	73889	14.0	.0	2D3	3.01	.19	.72	2.63	10.60			7	3	11	.13		.02			
493.0	498.0	73890	5.0	.0	2A4	2.89	.06	.82	3.20	13.70			7	3	11	.10		.02			
498.0	503.0	73891	5.0	.0	2A4	2.92	.03	1.35	3.15	31.20			2	1	4	.08		.03			
503.0	508.0	73892	5.0	.0	2A4	2.91	.06	1.88	3.15	31.50			2	1	4	.08		.03			
508.0	513.0	73893	5.0	.0	2A4	2.97	.08	1.20	3.35	43.50			2	1	4	.07		.03			
513.0	516.9	73894	3.9	.0	2A0	2.92	.07	1.17	1.85	47.30			2	1	4	.12		.03			

DDH: 77-01 UTM-N: 8573.3 UTM-E: 15213.8 UTM-ELEV: 4147.4 TOTAL DEPTH: 729.0 SECTION: 125
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----															S.G. W.R.
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %		
568.8	573.8	73906	5.0	.0	2G4	4.61	.14	4.39	4.35	65.10		.41	3	27	31	8.90		.16				
573.8	578.8	73907	5.0	.0	2G4	4.65	.13	6.28	6.48	83.80		.21	3	25	28	12.30		.12				
578.8	586.0	73908	7.2	.0	2E4	4.61	.11	1.76	2.80	19.00		.07	1	37	38	.10						
586.0	597.0	73909	11.0	.0	2E14	4.02	.02	2.02	3.49	21.00			2	32	34	.05						
597.0	601.0	73910	4.0	.0	2E1	3.55	.01	1.01	.49	11.40			1	29	30	.05						
601.0	607.0	73911	6.0	.0	2E1	3.07	.01	.01	.05	3.00			1	15	17	.05		.01				
607.0	612.0	73912	5.0	.0	2C3	3.70	.23	.97	2.85	33.40			5	20	26	.05		.07				
612.0	617.0	73913	5.0	.0	2C3	3.78	.26	.01	.68	7.00			5	24	29	.10		.08				
617.0	622.0	73914	5.0	.0	2E1	3.92	.48	.96	1.63	13.30			6	27	33	.10		.22				
622.0	627.0	73915	5.0	.0	2E1	3.98	.28	.30	1.44	5.00			6	28	35	.05		.14				
627.0	632.0	73916	5.0	.0	2E1	3.98	.22	1.43	2.32	8.70			6	26	33	.10		.16				
632.0	637.0	73917	5.0	.0	2E1	3.92	.50	.49	1.09	7.70			4	28	33	.05		.80				
637.0	642.0	73918	5.0	.0	2E1	3.82	.58	.27	.94	10.00			7	25	32	.05		.13				
642.0	647.0	73919	5.0	.0	2E84	4.08	.33	1.57	2.70	12.00		.07	6	27	34	.05		.18				
647.0	652.0	73920	5.0	.0	2E8	4.10	.29	1.17	2.20	8.70		.01	8	28	36	.05		.23				
652.0	657.0	73921	5.0	.0	2C2	3.88	.22	.27	1.04	5.60		.27	2	26	29	.05		.05				
657.0	662.0	73922	5.0	.0	2E8	4.35	.34	.92	1.95	7.30		.01	8	30	38	.05		.14				
662.0	667.0	73923	5.0	.0	2E1	3.75	.47	1.06	1.68	8.70		.07	5	23	29	.05		.13				
667.0	672.0	73924	5.0	.0	2E1	3.83	.22	.10	1.66	3.70			5	26	32	.05		.12				
672.0	675.0	73925	3.0	.0	2E1	4.01	.28	.04	1.34	4.40			5	30	36	.05		.12				
675.0	685.0	73926	10.0	.0	2F0	4.10	.31	1.44	4.33	8.00			5	29	35	.05		.09				
685.0	690.0	73927	5.0	.0	1D4	3.83	.12	1.42	5.38	13.30			6	22	28	.05		.09				

DDH: 77-02 UTM-N: 8468.9 UTM-E: 15315.3 UTM-ELEV: 4140.9 TOTAL DEPTH: 732.0 SECTION: 126
 RFE: S2 RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
76 474.0	476.0	73933	2.0	.0	2G24	4.41	.22	6.72	6.07	92.00			.27	12	14	26	10.80				.23
476.0	478.0	73934	2.0	.0	2E4	4.63	.24	4.66	3.50	54.70			.41	10	25	36	1.30				.26
478.0	484.0	73935	6.0	.0	2EG4	4.69	.12	5.63	5.16	71.40			.41	4	23	28	12.90				.14
0-4 484.0	488.0	73936	4.0	.0	2E1	4.81	.22	1.58	2.25	22.30			.01	2	37	40	1.70				.01
488.0	490.3	73937	2.3	.0	2EG	4.61	.06	2.50	4.78	25.70				2	32	34	6.20				.01
>6 490.3	491.3	73938	1.0	.0	2G4	4.55	.20	4.25	7.66	39.00			.07	2	20	23	17.00				.01
5-6 491.3	497.6	73939	6.3	.0	2E14	3.94	.26	2.21	2.80	27.70			.07	3	31	34	.10				.05
>6 497.6	498.4	73940	.8	.0	2G4	4.52	.02	3.55	7.02	38.70			.07	2	26	28	12.30				.01
0-4 498.4	499.6	73941	1.2	.0	2E4	4.81	.11	1.89	2.20	19.00			.07	1	40	41	.20				.01
>6 499.6	503.0	73942	3.4	.0	2G14	4.88	.05	4.78	8.26	44.10			.07	2	22	25	18.50				.01
0-4 503.0	505.0	73943	2.0	.0	2C0	4.20	.08	.80	1.50	9.60			.07	2	33	35	.10				
505.0	510.5	73944	5.5	.0	2F4	4.65	.18	6.38	8.46	74.70			.55	2	31	33	.05				.01
>6 510.5	515.0	73945	4.5	.0	2F4	4.67	.29	5.78	7.98	47.70			.14	2	32	34	.05				.01
515.0	520.0	73946	5.0	.0	2E4	4.98	.09	4.91	6.60	47.40			.21	2	34	36	.10				.01
0-4 520.0	526.4	73947	6.4	.0	2E0	3.75	.01	.44	.11	6.30			.14	1	27	29	.05				
4-5 526.4	531.0	73948	4.6	.0	2E4	4.02	.11	2.30	2.52	26.00			.01	2	31	33	.05				.05
>6 531.0	535.0	73949	4.0	.0	2F24	4.65	.06	4.90	5.03	42.00			.07	2	35	38	.05				.01
0-4 535.0	539.0	73950	4.0	.0	2E1	4.02	.01	.21	.10	5.00			.07	1	31	32	.05				
>6 539.0	543.9	73951	4.9	.0	2E4	4.44	.08	4.27	6.89	24.00			.07	2	32	35	.05				.02
0-4 543.9	548.3	73952	4.4	.0	2C0	3.56	.16	.21	.08	5.40			.07	1	24	26	1.30				.01
548.3	552.0	73953	3.7	.0	2E4	4.69	.04	3.30	7.35	22.70			.62	2	27	30	11.20				.01
>6 552.0	556.8	73954	4.8	.0	2E4	4.59	.05	4.41	6.05	26.70			.27	2	34	37	2.60				.01
556.8	561.0	73955	4.2	.0	2F2	4.37	.03	15.05	15.00	59.70			.14	3	23	27	.05				.01
561.0	563.0	73956	2.0	.0	2H9	3.75	.66	4.72	9.29	43.00			.48	22	3	26	.10				.08
563.0	568.0	73957	5.0	.0	2C8	4.17	.28	.54	1.91	10.30			.21	5	30	35	.05				.09
568.0	572.0	73958	4.0	.0	2C0	3.82	1.02	1.91	1.12	29.40			.14	4	29	34	.05				.08
0-4 572.0	577.0	73959	5.0	.0	2C0	3.65	.46	.36	.50	10.00			.01	5	30	36	.05				.07
577.0	582.0	73960	5.0	.0	2C0	3.64	.59	.88	1.60	15.40			.01	5	23	29	.05				.11
4-5 582.0	588.5	73961	6.5	.0	2E1	4.18	.27	1.55	3.05	16.60			.01	6	29	35	.05				.20
588.5	593.5	73962	5.0	.0	2EC	4.09	.27	1.86	2.95	17.70			.01	6	25	31	.05				.26
593.5	600.5	73963	7.0	.0	2C8	3.82	.67	.67	1.28	23.40			.07	6	21	28	.05				.15
600.5	602.5	73964	2.0	.0	2E1	4.41	.26	1.81	3.27	13.00			.07	7	32	39	.05				.18
0-4 602.5	607.0	73965	4.5	.0	2CE	4.20	.41	.47	1.11	16.60				4	31	36	.05				.08
607.0	612.0	73966	5.0	.0	2C0	3.55	.30	.37	.87	9.30				5	30	35	.10				.07
612.0	618.5	73967	6.5	.0	2C0	4.29	.30	.46	1.52	7.70				3	30	34	.10				.11
>6 618.5	620.5	73968	2.0	.0	2F0	4.44	.12	7.50	13.90	28.70			.07	6	24	30	.05				.21
4-5 620.5	626.5	73969	6.0	.0	2D0	3.68	.26	1.37	2.76	11.00				3	23	27	.05				.11
626.5	633.0	73970	6.5	.0	2C0	3.70	.29	.26	1.46	10.70				5	25	31	.05				.13
633.0	636.5	73971	3.5	.0	2E1	3.77	.27	.06	1.22	3.00			.03	4	26	31	.05				.10
0-4 636.5	639.5	73972	3.0	.0	2C0	3.85	.17	.05	1.92	3.30			.03	3	29	32	.05				.06
639.5	645.0	73973	5.5	.0	2E1	4.44	.30	.17	1.76	4.40			.03	7	34	41	.05				.10
645.0	650.0	73974	5.0	.0	2E1	4.57	.55	.38	1.60	6.00			.03	6	38	44	.10				.12
4-5 650.0	655.0	73975	5.0	.0	2E4	4.50	.40	1.66	2.56	10.00			.01	7	35	43	.05				.11
655.0	658.5	73976	3.5	.0	2F4	4.39	.06	6.73	14.10	30.10			.01	3	27	31	.05				.04
658.5	660.0	73977	1.5	.0	2D4	3.77	.12	4.95	14.10	30.10			.07	5	17	23	.05				.05
660.0	667.5	73978	7.5	.0	2F4	4.69	.05	4.61	9.80	22.40			.07	2	35	38	.05				.01
667.5	673.0	73979	5.5	.0	2D4	3.60	.06	7.38	17.00	28.70			.07	5	9	15	.05				.04
>6 673.0	678.0	73980	5.0	.0	2F14	3.80	.05	8.12	23.00	41.70			.07	4	8	12	.05				.02
678.0	683.0	73981	5.0	.0	2F14	3.56	.06	7.50	21.00	36.00			.14	6	9	15	.05				.04
683.0	687.0	73982	4.0	.0	2F14	3.64	.08	6.48	17.70	35.00				7	12	19	.05				.06
687.0	689.0	73983	2.0	.0	2H84	3.57	.25	5.41	16.40	29.70			.21	9	10	20	.05				.04

DDH: 77-02 UTM-N: 8468.9 UTM-E: 15315.3 UTM-ELEV: 4140.9 TOTAL DEPTH: 732.0 SECTION: 126
 RFE: S2 RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
689.0	690.7	73984	1.7	.0	2F14	3.91	.22	6.33	16.70	52.30		.21	10	11	21	.05		.10			
690.7	695.5	73985	4.8	.0	2C0	3.34	.89	.35	1.08	40.00			9	10	20	.10		.11			
695.5	700.5	73986	5.0	.0	2C0	3.24	.52	.14	1.24	40.70			9	11	20	.10		.06			

05MAR87 !THE IMPERIAL ANVIL!

ASSAY: (DEPTH SEQUENCE) DH015

PAGE:134

DDH: 77-03 UTM-N: 8380.4 UTM-E: 15406.4 UTM-ELEV: 4118.9 TOTAL DEPTH: 694.0 SECTION: 127
 RFE: S2 RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

---DEPTHS---						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
520.5	525.0	73992	4.5	.0	2F4	4.12	.10	4.30	9.80	31.10		.21	7	22	30	.05		.02			
525.0	530.0	73993	5.0	.0	2D4	3.88	.05	3.81	6.30	35.60		.34	4	25	29	.05		.04			
530.0	535.0	73994	5.0	.0	2E1	4.12	.20	.35	1.22	10.20			3	32	35	.05		.03			
535.0	540.0	73995	5.0	.0	2E1	4.03	.33	.11	.51	10.20			5	30	35	.05		.05			
540.0	545.0	73996	5.0	.0	2E4	3.97	.21	2.30	2.07	16.50		.14	1	29	31	.05		.01			
545.0	550.0	73997	5.0	.0	2E1	3.80	.07	.13	1.50	7.30			2	27	30	.05		.02			
550.0	555.0	73998	5.0	.0	2E1	3.83	.24	.33	.87	14.30			2	27	30	.05		.02			
555.0	560.0	73999	5.0	.0	2E1	3.94	.28	.64	.70	9.70			2	30	33	.05		.03			
560.0	566.0	74000	6.0	.0	2E1	4.02	.20	.91	1.28	21.50			3	30	33	.05		.04			
567.0	572.0	74002	5.0	.0	2E1	4.12	.23	.77	1.06	20.40			3	32	35	.05		.03			
572.0	577.0	74003	5.0	.0	2E1	3.95	.13	.81	2.46	9.70		.14	5	28	34	.05		.05			
577.0	582.0	74004	5.0	.0	2E1	4.08	.12	1.04	2.18	16.70		.27	5	31	36	.05		.06			
582.0	586.0	74005	4.0	.0	2E8	4.39	.20	.89	1.21	12.00		.99	7	32	40	.05		.10			
586.0	591.0	74006	5.0	.0	2E8	3.55	.21	1.66	2.84	22.40		.41	4	20	25	.05		.09			
591.0	595.0	74007	4.0	.0	2E1	3.97	.16	.52	2.18	6.00		.07	5	28	33	.05		.09			
595.0	598.0	74008	3.0	.0	2E1	4.22	.28	.01	.91	5.30			3	33	37	.05		.09			
598.0	603.0	74009	5.0	.0	2E1	3.77	.32	.06	.80	6.30			2	29	32	.05		.03			
603.0	609.0	74010	6.0	.0	2E1	3.78	.35	.12	.60	62.90			2	25	28	.05		.02			
609.0	615.0	74011	6.0	.0	2E1	3.97	.25	.23	.63	7.20			3	27	30	.05		.03			
615.0	621.0	74012	6.0	.0	2D4	3.51	.05	3.56	8.98	17.00			4	15	19	.10		.03			
621.0	627.0	74013	6.0	.0	2C0	2.81	.11	.96	2.14	10.40		.21	4	6	11	.10		.02			
627.0	635.0	74014	8.0	.0	2D4	3.39	.09	4.38	13.20	40.90		.07	7	6	13	.10		.03			
635.0	638.0	74015	3.0	.0	0Q9	2.96	.04	2.13	1.93	41.20		.89	2	3	6	.10		.04			

DDH: 77-07 UTM-N: 8060.0 UTM-E: 15635.9 UTM-ELEV: 4101.6 TOTAL DEPTH: 604.0 SECTION: 130
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %
368.4	369.7	74031	1.3	.0	2E8	4.26	.12	4.95	3.24	100.00			.69	4 20	25	5.07		.20		
369.7	375.0	74032	5.3	.0	2E8	4.95	.20	1.85	2.15	28.00			.82	12 27	40	.18		.62		
375.0	380.0	74033	5.0	.0	2E0	4.13	.17	1.22	1.06	17.20				5 28	33	.11		.16		
380.0	385.0	74034	5.0	.0	2E1	4.48	.02	1.07	1.03	11.40				2 36	38	.07		.04		
385.0	390.0	74035	5.0	.0	2C3	4.07	.01	.51	.42	8.60				1 30	32	.08		.03		
390.0	395.0	74036	5.0	.0	2C3	3.44	.01	.46	.31	9.30				1 20	22	.08		.01		
395.0	400.0	74037	5.0	.0	2E1	3.17	.01	.47	.44	7.60				1 32	34	.08		.02		
400.0	407.5	74038	7.5	.0	2C3	3.67	.04	.18	.23	6.30				1 27	28	.08		.01		
407.5	412.0	74039	4.5	.0	0Q0	3.18	.21	.66	.12	48.00				1 12	14	.08		.01		
412.0	415.6	74040	3.6	.0	2C3	3.97	.03	1.22	1.57	11.70			.21	1 30	31	.11		.01		
415.6	419.5	74041	3.9	.0	2F4	4.65	.13	6.60	10.00	63.40			.21	2 31	34	.20		.06		
419.5	425.0	74042	5.5	.0	2E4	4.08	.12	3.20	5.20	27.00			.14	2 27	29	.23		.03		
425.0	430.0	74043	5.0	.0	2E1	3.89	.13	.88	1.04	11.40			.34	1 32	33	.20		.01		
430.0	434.0	74044	4.0	.0	2C3	3.98	.10	.96	1.30	9.70			.14	1 30	31	.21		.02		
434.0	439.0	74045	5.0	.0	2E4	3.70	.44	3.45	2.17	29.40			.21	1 27	28	.07		.01		
439.0	443.4	74046	4.4	.0	2E4	4.31	.11	3.62	5.22	25.10			.07	1 31	32	.08		.01		
443.4	447.0	74047	3.6	.0	2F4	4.78	.03	10.05	13.20	67.60			.62	1 28	30	.06		.03		
447.0	452.0	74048	5.0	.0	2D4	3.53	.17	4.08	7.56	25.30			.14	3 17	20	.15		.23		
452.0	457.2	74049	5.2	.0	2DE	3.75	.14	2.20	4.20	14.60			.21	2 22	25	.11		.07		
457.2	458.7	74050	1.5	.0	2F4	4.20	.07	6.75	13.40	32.10			.41	4 23	27	.11		.21		
458.7	462.7	74051	4.0	.0	2D8	4.05	.31	7.25	8.95	41.60			.21	6 19	25	.12		.50		
462.7	466.0	74052	3.3	.0	2D8	4.10	.53	2.68	4.40	20.20				4 26	30	.15		.25		
466.0	471.0	74053	5.0	.0	2E1	4.13	.40	.41	.74	14.50				2 32	35	.03		.05		
471.0	477.3	74054	6.3	.0	2E1	3.98	.38	.50	.67	7.00				2 32	34	.04		.03		
477.3	482.0	74055	4.7	.0	2E1	4.17	.39	.99	1.60	7.80			.07	6 29	35	.08		.11		
482.0	487.0	74056	5.0	.0	2E8	4.12	.29	1.50	1.88	12.10			.01	7 30	38	.10		.24		
487.0	492.4	74057	5.4	.0	2E8	4.63	.29	.47	1.78	5.00				7 33	40	.11		.20		
496.6	502.2	74059	5.6	.0	2D3	3.71	.13	1.95	4.48	12.30		1.03	2 18	21	.11			.05		
502.2	506.0	74060	3.8	.0	2C3	4.37	.23	.10	1.18	3.40				5 29	34	.07		.18		
506.0	510.0	74061	4.0	.0	2C3	4.38	.31	.05	.89	3.90				2 29	32	.07		.10		
510.0	515.0	74062	5.0	.0	2C3	4.33	.68	.60	1.20	6.80				3 29	32	.10		.09		
515.0	518.0	74063	3.0	.0	2C3	4.28	.14	.82	1.89	5.40			.01	4 28	32	.12		.12		
518.0	522.2	74064	4.2	.0	2C3	4.42	.22	1.64	2.27	7.30			.01	4 28	32	.12		.12		
522.2	527.2	74065	5.0	.0	2C3	4.44	.50	.06	1.04	5.10			.01	1 32	34	.04		.03		
527.2	531.5	74066	4.3	.0	2C3	4.45	.20	1.45	2.90	5.80			.01	4 29	33	.06		.12		
531.5	537.3	74067	5.8	.0	2D4	3.91	.12	3.11	7.40	10.00			.01	3 21	25	.06		.04		
537.3	542.0	74068	4.7	.0	2D0	3.22	.10	2.09	4.60	23.40			.14	4 4	9	.27		.06		
542.0	551.0	74069	9.0	.0	2B0	2.72	.04	.96	2.18	13.10			.14	2 2	4	.27		.04		
551.0	556.0	74070	5.0	.0	2B0	2.84	.04	.94	2.01	11.00			.07	1 3	4	.64		.01		
556.0	561.0	74071	5.0	.0	2B0	2.82	.04	1.12	2.23	12.30				1 2	3	.58		.01		
561.0	566.0	74072	5.0	.0	2B5	2.50	.06	.89	2.28	13.00			.14	1 1	3	.49		.01		
566.0	571.0	74073	5.0	.0	2B0	2.79	.11	.68	2.08	12.40			.14	3 2	5	.37		.01		
571.0	577.0	74074	6.0	.0	2B0	2.71	.08	1.34	3.20	26.80			.27	2 1	3	.32		.02		
577.0	582.2	74075	5.2	.0	2B0	2.86	.09	.67	2.20	9.80			.14	2 2	5	.61		.04		
582.2	584.3	74076	2.1	.0	1D4	2.81	.05	.19	.23	2.80				3 3	6	.41		.13		
584.3	587.0	74077	2.7	.0	1D4	2.82	.02	.04	.07	1.10				3 1	4	.32		.12		
587.0	590.8	74078	3.8	.0	2A0	2.40	.01	.01	.05	1.20				3 1	4	.28		.17		
590.8	594.8	74079	4.0	.0	2B0	2.72	.03	.02	.10	2.60				2 1	4	.27		.10		
594.8	598.0	74080	3.2	.0	1D4	2.73	.05	.02	.11	3.90				2 1	3	.30		.07		

05MAR87 !THE IMPERIAL ANVIL!

ASSAY LISTING (DEPTH SEQUENCE) DH015

PAGE:136

DDH: 77-09 UTM-N: 8363.5 UTM-E: 14986.3 UTM-ELEV: 4096.7 TOTAL DEPTH: 765.0 SECTION: 125
 RFE: S2 RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %
516.8	520.8	74088	4.0	.0	2D0	3.34	.18	5.83	2.60	78.60		.96	2	9	12	.30		.03		
520.8	525.0	74089	4.2	.0	2G4	4.32	.06	3.52	10.30	34.10		.01	2	18	21	8.48		.03		
525.0	531.0	74090	6.0	.0	2G4	4.78	.03	2.12	4.46	19.80		.07	1	30	31	12.95		.02		
531.0	537.0	74091	6.0	.0	2G4	4.89	.09	3.95	6.62	37.90		.01	1	21	23	18.80		.06		
537.0	542.5	74093	5.5	.0	2D0	4.02	.17	1.83	3.40	24.00		.01	1	24	25	3.94		.03		
542.5	548.0	74094	5.5	.0	2D0	4.31	.08	2.82	5.63	44.00		.14	3	24	27	6.00		.09		
577.0	578.0	74096	1.0	.0	2H14	5.11	.03	2.42	5.96	32.10		.07	2	37	40	.20		.04		
578.0	581.3	74097	3.3	.0	2H2	4.61	.33	1.41	2.34	23.40		.01	29	15	45	.17		.10		
581.3	586.9	74098	5.6	.0	2C0	4.08	.05	1.40	.38	13.70		.07	2	31	33	.04		.04		
586.9	591.3	74099	4.4	.0	2E0	4.74	.19	1.02	1.19	15.60		.07	3	37	41	.05		.12		
591.3	596.3	74100	5.0	.0	2E8	4.75	.14	.76	1.36	9.50		.07	5	37	42	.02		.14		
596.3	599.3	74101	3.0	.0	2F0	4.82	.13	3.34	3.95	31.90		.07	4	36	40	.02		.09		
599.3	602.4	74102	3.1	.0	2F4	4.92	.06	6.00	12.30	45.30		.07	2	32	35	.02		.04		
602.4	607.4	74103	5.0	.0	2E34	5.00	.08	3.46	6.75	22.90		.07	2	37	40	.02		.04		
607.4	611.6	74104	4.2	.0	2E3	4.83	.26	2.78	4.14	21.60		.07	3	37	41	.02		.09		
611.6	616.6	74105	5.0	.0	2D3	4.30	.20	2.62	2.48	20.90		.07	3	31	35	.03		.09		
616.6	619.3	74106	2.7	.0	2E34	4.86	.09	2.46	3.90	19.60		.01	3	38	41	.03		.07		
619.3	623.3	74107	4.0	.0	2F4	4.91	.14	5.13	8.80	48.00		.06	3	32	35	.02		.13		
623.3	626.5	74108	3.2	.0	2F4	5.00	.11	4.50	6.86	31.20		.06	3	34	38	.03		.11		
626.5	630.0	74109	3.5	.0	2E4	4.54	.24	4.95	8.38	47.90			5	29	34	.04		.13		
630.0	634.5	74110	4.5	.0	2E4	4.36	.29	2.20	2.54	25.00			4	32	37	.05		.16		
634.5	639.0	74111	4.5	.0	2E4	4.63	.33	2.79	3.38	26.90			5	30	36	.05		.26		
639.0	642.0	74112	3.0	.0	2E4	4.74	.25	3.26	5.68	21.00			7	30	38	.03		.33		
642.0	646.9	74113	4.9	.0	2E4	4.65	.22	2.70	4.67	19.70			6	30	37	.04		.29		
646.9	650.0	74114	3.1	.0	2E4	4.14	.16	1.64	4.43	11.80		.03	6	27	33	.04		.20		
650.0	654.0	74115	4.0	.0	2E4	4.09	.34	1.38	4.20	12.70		.07	8	25	34	.03		.26		
654.0	657.5	74116	3.5	.0	2E34	4.29	.12	2.68	8.14	11.30		.07	7	26	33	.02		.24		
657.5	661.3	74117	3.8	.0	2E34	4.63	.12	3.88	7.60	12.00		.01	5	30	35	.02		.20		
661.3	666.3	74118	5.0	.0	2E34	5.05	.15	3.24	5.17	12.90		.07	1	39	40	.01		.02		
666.3	671.3	74119	5.0	.0	2E34	4.85	.13	3.86	5.56	18.20		.07	1	38	40	.04		.03		
671.3	675.3	74120	4.0	.0	2E34	4.78	.18	2.91	4.41	13.10		.01	1	40	41	.03		.02		
675.3	678.9	74121	3.6	.0	2E34	4.42	.08	2.41	4.47	12.50		.07	1	36	38	.07		.02		
678.9	683.9	74122	5.0	.0	2D0	3.19	.20	2.68	4.44	25.20		.14	7	9	16	.41		.06		
683.9	688.9	74123	5.0	.0	2D0	3.36	.40	2.69	6.73	29.60		.21	9	9	18	.41		.05		
688.9	692.5	74124	3.6	.0	2D0	3.36	.18	2.81	4.66	28.40		.14	7	16	24	.16		.06		

DDH: 77-10 UTM-N: 8165.0 UTM-E: 15223.0 UTM-ELEV: 4061.6 TOTAL DEPTH: 662.0 SECTION: 127
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
400.3	405.2	74129	4.9	.0	2C0	3.23	.11	.02	.15	5.40			2	19	21	.15					.03
405.2	408.0	74130	2.8	.0	2E0	4.55	.14	.01	.05	6.10			4	39	44	.03					.06
408.0	412.0	74131	4.0	.0	2A0	2.99	.19	.07	.51	5.50			3	13	16	.10					.07
412.0	416.0	74132	4.0	.0	2A0	3.22	.20	.36	.68	7.40			3	18	21	.09					.07
416.0	419.0	74133	3.0	.0	2A0	3.14	.34	.12	.26	5.20			1	19	20	.09					.02
419.0	421.0	74134	2.0	.0	2A0	3.68	.27	.37	3.97	7.80			1	20	21	.04					.02
421.0	422.0	74135	1.0	.0	2E4	4.22	.05	2.72	6.55	19.70		.01	1	33	34	.43					.02
432.0	436.0	74137	4.0	.0	2G4	4.61	.06	6.28	10.20	114.10		.41	2	16	19	20.97					.09
436.0	440.0	74138	4.0	.0	2G4	4.39	.07	5.32	9.20	83.70		.21	2	17	20	20.87					.11
440.0	444.0	74139	4.0	.0	2G4	4.48	.05	4.49	8.32	59.40		.07	2	12	14	26.21					.08
444.0	448.0	74140	4.0	.0	2G4	4.31	.06	6.46	8.86	73.60		.01	2	11	13	28.58					.07
448.0	452.0	74141	4.0	.0	2G4	4.33	.05	5.80	10.30	68.60		.01	2	8	10	32.28					.04
452.0	456.5	74142	4.5	.0	2G4	4.39	.05	6.21	9.47	76.70		.01	2	9	11	31.00					.04
456.5	462.0	74143	5.5	.0	2G4	4.35	.07	6.70	9.72	77.70		.07	2	9	12	30.69					.04
462.0	464.5	74144	2.5	.0	2E4	4.65	.08	10.10	3.72	124.50		.01	4	31	36	.61					.04
464.5	465.5	74145	1.0	.0	2J4	4.18	.29	5.30	8.78	76.80		.07	10	20	31	4.09					.14
465.5	467.0	74146	1.5	.0	2J4	4.29	.19	8.97	13.60	134.70		.34	10	12	23	9.98					.28
467.0	468.5	74147	1.5	.0	2J4	2.96	.04	11.00	16.40	218.90		.48	5	20	25	.49					.30
468.5	473.0	74148	4.5	.0	1D4	3.00	.10	1.20	2.10	30.50		.01	5	7	12	6.00					.11
473.0	478.0	74149	5.0	.0	1D4	2.92	.11	.18	.23	5.40			4	3	8	5.31					.09
478.0	480.0	74150	2.0	.0	1D4	3.39	.44	.48	.89	24.40			6	6	12	10.83					.11
480.0	484.0	74151	4.0	.0	2E0	4.72	.11	2.04	.71	44.00		.14	4	39	43	.56					.07
484.0	488.0	74152	4.0	.0	2E1	4.41	.19	.42	.19	10.50		.07	6	34	41	.10					.08
488.0	492.0	74153	4.0	.0	2E1	4.03	.34	1.66	2.39	35.30			13	24	37	.05					.35
492.0	496.0	74154	4.0	.0	2E1	4.31	.39	1.81	2.25	26.40		.14	10	26	37	.10					.18
496.0	501.5	74155	5.5	.0	2E0	4.61	.24	.64	1.30	11.30		.07	5	35	41	.03					.14
501.5	507.0	74156	5.5	.0	2E4	4.85	.09	2.50	4.53	21.40		.07	2	39	42	.02					.04
507.0	511.0	74157	4.0	.0	2F4	5.08	.04	7.75	10.20	56.80		.01	2	34	36	.02					.01
511.0	515.0	74158	4.0	.0	2F4	5.05	.10	5.87	9.68	47.50		.07	3	34	37	.02					.05
515.0	518.0	74159	3.0	.0	2F4	4.74	.11	5.63	6.90	67.10		.07	4	34	38	.03					.18
518.0	522.0	74160	4.0	.0	2E0	4.44	.35	3.02	1.80	35.40		.14	6	33	40	.03					.27
522.0	524.0	74161	2.0	.0	2E0	4.95	.15	1.77	.88	55.90		.07	2	23	26	.02					.05
524.0	525.0	74162	1.0	.0	2H0	4.35	.12	1.88	1.82	27.50		.07	12	25	38	.06					.10
525.0	528.0	74163	3.0	.0	2E4	4.39	.15	4.43	3.41	60.80		.34	6	29	36	.04					.14
528.0	531.0	74164	3.0	.0	2FE	4.87	.12	4.05	5.61	48.50		.34	4	33	37	.09					.10
531.0	534.0	74165	3.0	.0	2E0	4.47	.10	1.08	2.64	18.10		.27	4	33	37	.02					.10
534.0	537.0	74166	3.0	.0	2E4	4.09	.07	3.04	4.11	36.10		.41	2	28	31	.05					.05
537.0	542.6	74167	5.6	.0	2E4	4.78	.07	3.24	3.92	28.40		.21	2	38	41	.03					.05
542.6	546.5	74168	3.9	.0	2E4	4.61	.07	3.32	5.48	29.30		.07	1	35	36	.03					.03
546.5	550.5	74169	4.0	.0	2E1	4.63	.11	2.10	2.22	17.80		.14	3	35	39	.04					.09
550.5	554.5	74170	4.0	.0	2E8	4.26	.13	.94	1.90	10.10		.07	6	29	35	.03					.17
554.5	559.5	74171	5.0	.0	2F4	4.44	.09	4.20	10.00	18.20		.55	4	29	33	.02					.14
559.5	564.5	74172	5.0	.0	2F0	4.39	.10	2.23	6.11	9.00		.07	5	30	35	.03					.15
564.5	566.5	74173	2.0	.0	2E1	3.95	.20	.21	2.19	4.80			4	29	33	.02					.09
566.5	572.0	74174	5.5	.0	2E1	4.11	.13	.38	1.54	4.20			5	27	33	.02					.11
572.0	577.0	74175	5.0	.0	2E1	4.26	.11	.61	2.25	5.00		.21	5	30	35	.07					.11
577.0	582.0	74176	5.0	.0	2FE4	4.50	.08	4.41	11.10	13.50		.14	2	30	32	.03					.04
582.0	587.0	74177	5.0	.0	2F4	5.08	.07	5.31	9.60	17.70		.07	2	34	36	.02					.03
587.0	592.0	74178	5.0	.0	2F4	5.21	.01	6.38	10.40	23.40		.07	1	34	36	.01					.02
592.0	597.0	74179	5.0	.0	2F4	5.78	.03	4.07	7.23	14.80		.07	1	37	38	.01					.01

05MAR87 !THE IMPERIAL ANVIL!

ASSAY LISTING (DEPTH SEQUENCE) DH015

PAGE:138

DDH: 77-10 UTM-N: 8165.0 UTM-E: 15223.0 UTM-ELEV: 4061.6 TOTAL DEPTH: 662.0 SECTION: 127
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
597.0	609.0	74180	12.0	.0	2F4	4.88		4.46	10.10	21.90		.01	2	31	33	.02		.02			
609.0	614.0	74181	5.0	.0	2D4	3.38	.05	3.72	9.85	27.20		.14	6	7	14	.30		.04			
614.0	619.0	74182	5.0	.0	2D4	3.51	.10	3.00	7.68	24.00		.07	11	8	20	.11		.02			
619.0	623.0	74183	4.0	.0	2C0	3.08	.06	1.36	2.27	16.20		.14	5	5	10	.29		.02			
623.0	625.6	74184	2.6	.0	2C0	2.92	.56	.60	1.94	37.90		.07	6	4	10	.18		.05			
625.6	628.0	74185	2.4	.0	1E0	2.77	.39	.22	.50	19.70			3	2	5	.25		.03			

DDH: 77-12 UTM-N: 7802.6 UTM-E: 15208.3 UTM-ELEV: 4014.7 TOTAL DEPTH: 402.0 SECTION: 129
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----		-----ASSAYS-----																			
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
228.2	231.2	74191	3.0	.0	2C3	3.55	.10	.30	.54	5.40			2	22	24	.23					.04
231.2	234.7	74192	3.5	.0	2AE4	4.08	.04	1.70	5.88	8.60			.21	2	28	30	.03				.03
234.7	237.3	74193	2.6	.0	2A4	3.54	.05	4.23	10.50	25.10			.41	2	14	16	.11				.02
237.3	241.0	74194	3.7	.0	2A4	3.55	.05	3.46	13.73	20.40			.34	3	13	16	.11				.03
241.0	244.0	74195	3.0	.0	2D0	3.53	.06	1.85	7.25	22.30			.48	3	16	19	.37				.05
244.0	247.3	74196	3.3	.0	2GH	4.49	.32	6.58	6.00	39.90			.41	14	17	32	7.82				.49
247.3	250.6	74197	3.3	.0	2G4	3.98	.17	10.35	5.52	51.00			.48	9	10	20	3.58				.36
250.6	253.6	74198	3.0	.0	2F4	4.55	.14	8.28	7.00	51.30			.34	9	21	31	5.49				.49
253.6	257.0	74199	3.4	.0	2B0	3.04	.14	.90	1.55	11.30			.07	5	3	8	7.36				.15
257.0	258.0	74200	1.0	.0	2G84	4.68	.08	7.04	6.00	64.20			.21	9	23	33	7.38				.58
258.0	259.7	74201	1.7	.0	2GH4	4.53	.28	5.31	5.27	83.50			.14	24	6	30	12.08				.59
259.7	263.5	74202	3.8	.0	2A4	3.10	.08	2.57	2.74	26.60			.07	6	4	11	3.20				.22
263.5	271.7	74203	8.2	.0	2B0	2.92	.03	.20	.54	1.50			.07	3	3	7	7.25				.07
271.7	275.7	74204	4.0	.0	2D0	3.56	.14	2.29	6.94	35.10			.07	9	14	24	1.56				.10
275.7	280.5	74205	4.8	.0	2D0	3.21	.16	1.86	4.75	26.10			.01	7	10	18	.59				.05
280.5	286.0	74206	5.5	.0	2F0	5.21	.10	3.05	5.15	22.00			.01	2	37	39	.05				.04
286.0	290.3	74207	4.3	.0	2H4	4.48	.58	4.82	7.46	48.70			.01	21	16	38	.04				.11
290.3	292.4	74208	2.1	.0	2F84	4.74	.13	5.73	9.85	55.10			.01	6	29	36	.03				.09
292.4	297.4	74209	5.0	.0	2D0	2.82	.10	.71	4.30	13.60			.07	6	4	10	.38				.06
297.4	302.4	74210	5.0	.0	2D0	2.76	.08	1.81	2.54	33.40			.01	4	3	8	.51				.04
302.4	307.0	74211	4.6	.0	2D0	2.82	.10	1.58	3.64	29.20			.07	7	2	9	.55				.03
307.0	310.0	74212	3.0	.0	2D0	3.08	.13	1.96	7.08	36.30			.07	13	1	15	.26				.03
310.0	315.0	74213	5.0	.0	2H4	4.18	.55	2.91	7.40	50.80			.07	46		46	.03				.03
315.0	319.7	74214	4.7	.0	2H4	4.10	.56	2.16	5.26	35.20			.07	49		49	.03				.03
319.7	321.0	74215	1.3	.0	2D0	3.17	.32	2.96	5.05	56.90			.07	19		19	.15				.04
321.0	324.0	74216	3.0	.0	2H0	4.14	.52	.32	.55	8.60			.27	47		47	.04				.02
324.0	329.0	74217	5.0	.0	2D0	3.20	.17	.84	5.54	13.80			.14	17	4	21	.17				.03
329.0	334.0	74218	5.0	.0	2D0	3.15	.10	1.57	4.97	27.20			.07	14	1	16	.45				.02
334.0	339.0	74219	5.0	.0	2D0	3.06	.13	3.66	5.64	60.30			.07	11	20	31	.56				.03
339.0	344.0	74220	5.0	.0	2A0	2.71	.08	.87	2.69	21.20			.07	5	3	9	.50				.02
344.0	349.0	74221	5.0	.0	2A4	2.78	.07	1.54	2.83	39.50			.21	7	2	10	.54				.01
349.0	354.0	74222	5.0	.0	2A0	2.89	.05	1.04	2.69	23.90			.14	3	4	7	.37				
354.0	359.5	74223	5.5	.0	2A4	2.66	.05	1.75	2.79	27.40			.21	2	1	3	.47				.01

05MAR87 !THE IMPERIAL ANVIL!

ASSAY LISTING (DEPTH SEQUENCE) DH015

PAGE:140

DDH: 77-13 UTM-N: 7974.9 UTM-E: 14986.7 UTM-ELEV: 4018.2 TOTAL DEPTH: 543.0 SECTION: 127
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %
376.0	380.0	74229	4.0	.0	2C0	3.35	.26	.02	.09	7.90			4	17	21	.12		.03		
380.0	385.0	74230	5.0	.0	2C0	3.58	.14	.02	.05	10.90			2	19	21	.09		.04		
385.0	389.0	74231	4.0	.0	2C0	3.59	.59	.04	.07	16.70			2	21	23	.05		.02		
389.0	393.5	74232	4.5	.0	2C0	3.52	.44	.12	.18	23.70			2	22	25	.08		.04		
393.5	395.5	74233	2.0	.0	2D0	4.55	.19	3.46	5.64	57.00			3	22	26	.33		.10		
395.5	399.5	74234	4.0	.0	2G4	4.68	.16	5.93	5.45	78.80			6	21	28	10.69		.18		
399.5	403.0	74235	3.5	.0	2G4	4.37	.27	5.44	5.17	75.30			10	19	29	10.51		.20		
403.0	404.5	74236	1.5	.0	2H4	4.36	.59	3.36	3.11	62.20			18	17	36	.83		.18		
404.5	405.8	74237	1.3	.0	2G4	4.63	.11	7.78	6.43	105.00			3	23	27	12.60		.16		
405.8	409.7	74238	3.9	.0	2H4	4.14	.45	4.56	4.21	77.70			29	8	38	4.32		.19		
409.7	411.0	74239	1.3	.0	2D4	3.31	.25	9.51	7.04	116.80			7	6	13	.52		.16		
436.0	440.0	74241	4.0	.0	2D4	3.47	.13	5.97	7.65	83.60			11	9	21	.25		.17		
440.0	444.0	74242	4.0	.0	2B4	3.17	.06	7.81	6.51	110.10			.07	6	6	13	.20	.15		
444.0	447.0	74243	3.0	.0	2B4	3.02	.07	6.07	5.41	94.30			.01	5	4	10	.92	.14		
447.0	450.0	74244	3.0	.0	2B0	2.79	.02	1.15	1.87	22.10			.01	3	2	6	2.07	.08		
450.0	453.0	74245	3.0	.0	2D0	3.62	.20	3.84	6.08	66.80			.07	11	13	24	1.21	.12		
453.0	457.0	74246	4.0	.0	2D4	3.90	.25	3.91	7.61	65.30			.07	13	18	32	.53	.11		
457.0	459.0	74247	2.0	.0	2B0	3.14	.16	2.61	2.93	30.40			.07	7	9	16	1.31	.08		
459.0	462.0	74248	3.0	.0	2B0	2.96	.06	1.93	2.54	21.40			.03	4	5	9	.88	.06		
462.0	465.0	74249	3.0	.0	2B0	3.22	.07	2.85	5.01	39.50			.01	7	7	15	1.63	.09		
465.0	470.0	74250	5.0	.0	2D0	3.87	.32	2.43	3.12	43.90			.01	15	19	35	.38	.11		
470.0	474.0	74251	4.0	.0	2E14	4.60	.37	2.23	3.05	40.20			.01	15	25	40	.10	.12		
474.0	477.0	74252	3.0	.0	2E14	4.18	.13	3.76	5.54	49.10			.01	9	26	36	.38	.10		
477.0	482.6	74253	5.6	.0	2E4	4.75	.12	3.45	5.29	46.00			.07	5	32	38	.09	.06		
482.6	485.0	74254	2.4	.0	2H4	4.32	.16	4.91	10.00	78.60			.01	19	14	34	.07	.09		
485.0	487.0	74255	2.0	.0	2D0	3.09	.07	1.70	2.70	18.60			.01	9	7	16	.39	.09		
487.0	491.0	74256	4.0	.0	2H4	4.23	.23	4.49	7.53	50.10			.01	13	23	37	.04	.09		
491.0	496.4	74257	5.4	.0	2F4	4.63	.04	4.86	9.38	35.20				5	32	37	.03	.07		
496.4	501.4	74258	5.0	.0	2F4	4.76	.05	6.08	10.26	42.20			.01	4	32	37	.02	.06		
501.4	505.8	74259	4.4	.0	2F0	4.67	.08	3.14	6.49	23.90			.01	5	35	41	.03	.05		
505.8	510.5	74260	4.7	.0	2H4	4.37	.20	4.00	8.78	30.80			.07	8	28	37	.03	.10		
510.5	515.5	74261	5.0	.0	2D0	3.19	.09	2.62	6.94	32.40			.07	7	6	13	.24	.10		
515.5	520.5	74262	5.0	.0	2D0	3.03	.08	1.70	4.17	27.70			.07	4	3	8	.36	.05		
520.5	525.5	74263	5.0	.0	2D0	3.18	.08	1.24	4.73	25.10			.01	6	5	12	.38	.07		
525.5	531.0	74264	5.5	.0	2D0	3.04	.07	.90	3.80	22.80			.07	5	5	11	.31	.05		
531.0	536.7	74265	5.7	.0	2D0	3.14	.05	2.35	4.86	38.10			.07	5	3	8	.30	.04		

DDH: 77-14 UTM-N: 7978.7 UTM-E: 15357.8 UTM-ELEV: 4023.4 TOTAL DEPTH: 323.0 SECTION: 129
 RFE: S2 RFE DIR: 240 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
293.0	298.0	74268	5.0	.0	2C0	3.24	.20	.45	1.21	9.70				6	13	19	.37				.06
298.0	302.0	74269	4.0	.0	****	3.42	.05	.10	.05	4.40				2	2	4	.15				.02
302.0	307.0	74270	5.0	.0	2AC	3.10	.21	.05	.16	10.10				1	8	10	.21				.02
307.0	310.5	74271	3.5	.0	2AC	3.34	.21	.10	.49	13.40				1	12	13	.18				.01
310.5	314.0	74272	3.5	.0	2AC	3.80	.04	.72	2.78	8.50		.14	1	23	24	.11				.02	
314.0	318.5	74273	4.5	.0	2F0	4.00	.24	4.71	9.32	75.60		.14	7	16	24	2.31				.16	

DDH: 77-15 UTM-N: 7794.9 UTM-E: 14799.4 UTM-ELEV: 4016.0 TOTAL DEPTH: 565.0 SECTION: 127
 RFE: S2 RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
400.0	405.0	74278	5.0	.0	2C0	3.14	.29	.92	2.03	14.00		.34	6	10	16	.12		.04			
405.0	410.0	74279	5.0	.0	2A4	3.51	.13	1.81	5.79	17.50		.48	4	16	20	.12		.03			
410.0	416.0	74280	6.0	.0	2A4	3.34	.11	1.83	6.93	17.90		.27	3	15	19	.50		.04			
416.0	420.6	74281	4.6	.0	2D4	4.45	.25	5.74	6.59	57.20		.07	9	17	27	9.09		.31			
420.6	424.4	74282	3.8	.0	2B0	2.90	.12	1.50	.42	9.00		.01	3	2	5	9.95		.05			
424.4	427.9	74283	3.5	.0	2D0	3.22	.18	1.46	2.86	26.10		.01	5	7	13	9.06		.15			
427.9	431.2	74284	3.3	.0	2D4	3.52	.19	4.59	5.73	34.90		.01	10	8	18	6.58		.24			
431.2	436.2	74285	5.0	.0	2H14	4.29	.28	5.26	6.23	69.90		.07	18	16	35	4.81		.23			
436.2	441.0	74286	4.8	.0	2H14	4.16	.24	4.29	6.50	60.80		.07	18	14	33	1.39		.13			
441.0	446.0	74287	5.0	.0	2B0	3.01	.12	.90	2.43	14.10		.01	5	4	10	.76		.05			
446.0	450.0	74288	4.0	.0	2B4	3.05	.12	1.44	3.95	23.30		.01	4	5	9	.45		.04			
450.0	454.0	74289	4.0	.0	2B0	2.95	.08	1.05	2.52	21.10		.01	4	5	10	.72		.04			
454.0	458.0	74290	4.0	.0	2B0	2.94	.09	.69	1.99	16.20		.07	4	2	7	.64		.05			
458.0	463.0	74291	5.0	.0	2E4	4.63	.31	3.03	4.58	48.80		.07	12	28	41	.04		.10			
463.0	468.0	74292	5.0	.0	2E4	4.63	.35	3.23	5.31	50.30		.01	13	27	40	.03		.09			
468.0	471.0	74293	3.0	.0	2E4	4.21	.48	5.73	9.90	54.80		.14	16	18	34	.09		.12			

DDH: 77-16 UTM-N: 7986.5 UTM-E: 14589.4 UTM-ELEV: 4007.0 TOTAL DEPTH: 670.0 SECTION: 125
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----						-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
430.0	433.5	74299	3.5	.0 2A0	2.60	.01		.20	.10			3	1	4	.25		.08			
433.5	437.0	74300	3.5	.0 2B2	2.68	.07	.11	.35	3.00			3	5	8	.87		.03			
437.0	439.5	74301	2.5	.0 1D4	2.97	.17	.13	.27	4.50			8	12	20	.54		.04			
439.5	445.0	74302	5.5	.0 2A0	2.75	.13	.23	.43	5.30			6	7	14	.21		.04			
445.0	450.0	74303	5.0	.0 2C0	2.88	.40	1.08	2.82	13.80		.07	6	8	14	.28		.07			
450.0	455.0	74304	5.0	.0 2FG4	4.56	.22	5.73	7.21	76.60		.07	8	24	32	6.76		.22			
455.0	460.0	74305	5.0	.0 2FG4	4.59	.13	5.29	6.44	65.10		1.30	5	30	36	2.29		.17			
460.0	463.5	74306	3.5	.0 2DG7	3.51	.26	3.71	4.97	53.60		.01	14	7	21	6.69		.12			
463.5	467.0	74307	3.5	.0 2DG7	3.36	.26	2.36	4.23	35.00		.27	6	9	15	10.99		.14			
467.0	472.0	74308	5.0	.0 2G4	4.77	.20	5.87	6.22	82.50		.34	6	26	33	5.13		.21			
472.0	477.0	74309	5.0	.0 2G0	4.51	.27	4.40	4.90	65.20		.48	6	23	29	15.41		.32			
477.0	482.0	74310	5.0	.0 2G4	4.55	.19	5.76	6.59	82.40		.62	5	21	26	17.67		.29			
482.0	487.0	74311	5.0	.0 2G4	4.67	.22	5.44	6.98	80.70		.07	6	19	26	20.15		.28			
487.0	492.0	74312	5.0	.0 2G4	4.56	.22	5.60	5.94	90.10		.34	7	22	29	13.42		.31			
492.0	497.5	74313	5.5	.0 2G4	4.60	.26	5.89	6.44	85.10		.07	12	24	36	2.69		.19			
497.5	501.5	74314	4.0	.0 2H4	4.31	.22	6.81	8.35	99.70		.14	15	18	33	1.55		.14			
501.5	506.5	74315	5.0	.0 2D0	3.01	.15	2.00	4.55	32.90		.01	8	5	14	.20		.05			
506.5	510.0	74316	3.5	.0 2C0	2.84	.14	.90	3.06	14.40		.01	6	4	10	.22		.03			
510.0	514.5	74317	4.5	.0 2D0	3.03	2.00	.44	5.43	69.90		1.30	13	4	18	.23		.06			
514.5	519.0	74318	4.5	.0 2A0	2.67	.27	.37	1.50	13.90		.07	5	1	6	.40		.06			
519.0	522.0	74319	3.0	.0 2A0	2.61	.12	.05	.19	3.90		.01	5		6	.67		.08			

DDH: 77-17 UTM-N: 8190.0 UTM-E: 14784.1 UTM-ELEV: 4026.3 TOTAL DEPTH: 650.0 SECTION: 125
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----						-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
459.0	464.0	74325	5.0	.0 2C0	2.95	.26	.10	.11	9.80		.33	8	11	20	.43		.06			
464.0	469.0	74326	5.0	.0 2D4	3.21	.12	2.00	8.87	34.10		.14	6	9	15	.16		.09			
469.0	473.0	74327	4.0	.0 2DB4	3.28	.13	2.05	4.81	36.00		.21	8	7	15	5.03		.18			
473.0	475.0	74328	2.0	.0 2G4	4.20	.07	6.43	6.47	109.30		.82	8	10	19	19.10		.32			
475.0	478.0	74329	3.0	.0 2H64	3.88	.04	4.81	5.18	66.20		.41	4	10	14	22.18		.17			
478.0	481.0	74330	3.0	.0 2H6	4.33	.24	5.19	4.00	77.50		.41	20	10	30	6.72		.44			
481.0	485.0	74331	4.0	.0 2G4	4.53	.12	6.57	4.97	102.70		.41	12	18	30	6.94		.38			
485.0	490.0	74332	5.0	.0 2G4	4.61	.08	7.24	6.13	97.30		.21	6	16	22	21.75		.33			
490.0	494.0	74333	4.0	.0 2G74	4.54	.20	7.67	5.44	108.00		.07	25	3	29	16.92		.42			
494.0	498.0	74334	4.0	.0 2G74	4.15	.32	5.41	5.23	78.80		.07	19	5	25	18.63		.36			
527.7	529.0	74336	1.3	.0 2D0	2.95	.05	1.30	1.96	25.40		.01	6	4	10	2.54		.13			
529.0	532.3	74337	3.3	.0 2B0	2.88	.05	1.11	1.70	19.60		.01	3	4	8	3.19		.07			
532.3	537.2	74338	4.9	.0 2D4	3.95	.22	4.64	7.33	77.00		.01	14	14	29	.11		.20			
537.2	540.2	74339	3.0	.0 2C0	2.81	.12	.70	.39	16.60		.01	2	5	7	.05		.02			
540.2	543.5	74340	3.3	.0 2D4	3.40	.11	9.26	17.00	17.00		.01	6	4	10	.11		.15			
543.5	548.5	74341	5.0	.0 2H8	4.30	.40	3.51	3.86	47.00		.01	32	12	44	.06		.11			
548.5	553.5	74342	5.0	.0 2H84	4.22	.45	5.45	6.27	80.70		.01	28	11	39	.19		.09			
553.5	555.1	74343	1.6	.0 2E14	4.70	.28	2.00	2.67	28.90		.01	11	31	43	.08		.09			
555.1	560.1	74344	5.0	.0 2F4	4.83	.09	5.88	9.57	49.00		.01	2	34	36	.04		.06			
560.1	564.1	74345	4.0	.0 2F0	5.04	.46	2.42	3.57	26.40		.01	1	41	43	.05		.02			
564.1	568.5	74346	4.4	.0 2F4	4.62	.07	3.75	7.11	27.30		.01	1	36	38	.02		.02			
568.5	573.5	74347	5.0	.0 2H84	4.53	.30	4.39	7.21	40.10		.01	23	18	41	.04		.08			
573.5	578.0	74348	4.5	.0 2H8	4.23	.46	2.50	3.75	29.30		.01	17	23	40	.03		.15			
578.0	581.0	74349	3.0	.0 2F0	4.55	.12	3.52	4.55	34.40		.01	6	32	38	.02		.09			
581.0	584.7	74350	3.7	.0 2F0	4.34	.22	3.14	4.88	28.50		.07	4	33	37	.03		.07			
584.7	587.0	74351	2.3	.0 2D0	3.01	.10	1.45	6.56	22.20		.01	6	7	14	.31		.04			
587.0	592.0	74352	5.0	.0 2C0	2.86	.08	1.68	2.18	19.00		.01	3	4	8	.29		.02			
592.0	597.0	74353	5.0	.0 2D0	2.89	.12	1.88	2.78	25.10		.01	4	4	8	.33		.03			
597.0	600.0	74354	3.0	.0 2D0	3.09	.13	2.23	1.95	26.10		.06	8	7	16	.38		.10			
600.0	604.0	74355	4.0	.0 2D0	3.33	.20	1.60	2.93	30.60		.07	8	11	20	.18		.09			
604.0	608.6	74356	4.6	.0 2DB	2.83	.04	2.29	4.69	41.40		.07	2	3	5	.19		.03			
608.6	611.0	74357	2.4	.0 2A0	2.71	.06	1.07	1.88	21.90		.07	3	3	6	.18		.04			
611.0	614.0	74358	3.0	.0 2A0	2.75	.08	1.59	2.38	23.40		.01	3	3	6	.23		.04			
615.7	617.6	74360	1.9	.0 2B4	3.07	.06	7.53	8.00	154.20		.07	5	2	7	.08		.10			
617.6	622.4	74361	4.8	.0 1D4	2.82	.06	.07	.07	6.00			4	3	7	.15		.04			

DDH: 77018 UTM-N: 9790.4 UTM-E: 14417.4 UTM-ELEV: 3831.1 TOTAL DEPTH: 297.0 SECTION:
 RFE: RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
26.0	31.0	74365	5.0	.0	****	4.65	.11	1.52	3.70	9.20			5	28	33	.04		.11			
31.0	36.0	74366	5.0	.0	****	4.18	.25	.14	1.79	6.30			4	32	37	.01		.08			
36.0	40.0	74367	4.0	.0	****	3.77	.17	.12	1.05	5.10			3	28	31	.02		.06			
40.0	43.0	74368	3.0	.0	****	3.95	.17	.61	1.03	6.20			3	30	33	.01		.07			
43.0	47.0	74369	4.0	.0	****	4.12	.16	.13	1.88	5.80			4	29	33	.02		.09			
47.0	50.0	74370	3.0	.0	****	3.59	.13	1.50	7.13	7.40			3	23	26	.03		.05			
50.0	53.5	74371	3.5	.0	****	4.00	.08	4.68	10.51	15.80			3	23	26	.02		.04			
53.5	56.0	74372	2.5	.0	****	3.76	.14	1.27	4.10	6.50			3	23	26	.01		.07			
56.0	59.0	74373	3.0	.0	****	4.38	.14	.17	3.36	4.20			5	31	37	.01		.14			
59.0	62.0	74374	3.0	.0	****	4.25	.14	.29	2.15	6.20			6	33	39	.02		.15			
62.0	66.0	74375	4.0	.0	****	4.19	.04	.63	2.60	4.90			2	33	36	.03		.06			
66.0	69.0	74376	3.0	.0	****	4.17	.05	.86	3.68	5.40			2	32	34	.03		.04			
69.0	70.5	74377	1.5	.0	****	3.71	.05	3.77	12.37	13.40			3	18	21	.09		.03			
70.5	71.5	74378	1.0	.0	****	3.14	.04	1.25	3.30	6.20			1	17	19	.03		.02			
71.5	76.5	74379	5.0	.0	****	3.48	.04	7.73	20.00	28.00			4	11	16	.11		.02			
76.5	81.5	74380	5.0	.0	****	3.88	.04	.54	.50	4.50			1	25	26	.03		.01			
81.5	86.5	74381	5.0	.0	****	3.59	.03	.20	.31	4.20			1	25	27	.02		.02			
86.5	91.0	74382	4.5	.0	****	3.71	.03	5.22	9.89	22.50			2	18	21	.10		.02			
91.0	96.0	74383	5.0	.0	****	3.33	.04	1.37	7.43	11.80			3	17	20	.11		.03			
96.0	101.0	74384	5.0	.0	****	3.41	.03	3.98	10.11	18.20			2	16	19	.11		.02			
101.0	106.0	74385	5.0	.0	****	3.66	.03	4.29	9.36	20.00			3	18	21	.09		.03			
106.0	113.0	74386	7.0	.0	****	3.43	.04	1.76	7.25	13.60			3	16	19	.13		.03			
113.0	118.0	74387	5.0	.0	****	3.25	.04	1.94	4.73	16.10			2	14	17	.19		.02			
118.0	123.0	74388	5.0	.0	****	3.20	.02	.50	1.03	6.20			2	15	17	.22		.02			
123.0	128.0	74389	5.0	.0	****	3.56	.03	.90	4.14	8.90			2	24	26	.07		.01			
128.0	132.0	74390	4.0	.0	****	4.73	.02	2.08	6.75	12.80			2	38	41	.02		.02			
132.0	137.0	74391	5.0	.0	****	4.41	.03	7.66	16.60	45.10			3	26	29	.02		.02			
137.0	141.0	74392	4.0	.0	****	4.24	.05	9.37	22.80	50.60			4	18	23	.02		.03			
141.0	145.0	74393	4.0	.0	****	3.25	.03	.83	1.95	11.90			2	16	19	.18		.03			
145.0	149.0	74394	4.0	.0	****	3.40	.03	.23	.82	5.20			3	18	21	.17		.02			
149.0	153.0	74395	4.0	.0	****	3.55	.11	.65	3.21	8.90			5	22	28	.18		.04			
153.0	157.0	74396	4.0	.0	****	3.36	.06	2.76	6.89	24.10			3	15	19	.16		.03			
157.0	161.0	74397	4.0	.0	****	3.37	.04	3.69	14.70	32.70			3	12	16	.13		.03			
161.0	165.0	74398	4.0	.0	****	3.25	.03	2.43	9.00	24.10			2	14	16	.12		.02			
165.0	169.0	74399	4.0	.0	****	3.43	.03	2.22	8.27	19.80			3	18	21	.11		.02			
169.0	174.0	74400	5.0	.0	****	4.54	.02	1.38	3.60	9.70			1	41	42	.02		.02			
174.0	179.0	74401	5.0	.0	****	4.73	.02	1.38	2.48	10.70			2	42	44	.02		.02			
179.0	184.0	74402	5.0	.0	****	3.11	.11	2.85	10.61	26.80			7	6	13	.18		.04			
184.0	187.0	74403	3.0	.0	****	4.69	.04	.54	1.50	6.60			1	44	45	.01		.02			
187.0	192.0	74404	5.0	.0	****	3.37	.04	3.37	9.91	23.10			3	16	20	.10		.02			
192.0	195.0	74405	3.0	.0	****	4.29	.02	2.18	4.11	13.60			2	36	38	.02		.02			
195.0	200.0	74406	5.0	.0	****	4.49	.02	1.72	3.50	8.90			1	39	41	.03		.03			
200.0	205.0	74407	5.0	.0	****	4.08	.03	2.14	5.21	14.80			2	32	34	.05		.02			
205.0	210.0	74408	5.0	.0	****	4.27	.02	3.26	6.75	19.20			2	35	37	.02		.03			
210.0	214.0	74409	4.0	.0	****	3.73	.04	2.49	9.23	20.00			3	22	25	.02		.04			
214.0	219.0	74410	5.0	.0	****	3.47	.05	2.67	8.77	17.90			4	16	20	.09		.04			
219.0	224.0	74411	5.0	.0	****	3.26	.11	2.90	4.85	28.00			2	17	19	.09		.03			
224.0	229.0	74412	5.0	.0	****	3.22	.11	.32	2.40	7.50			2	14	16	.11		.02			
229.0	234.0	74413	5.0	.0	****	3.19	.21	.62	5.38	17.00			5	8	14	.10		.04			
234.0	239.0	74414	5.0	.0	****	3.32	.17	3.02	10.51	22.70			6	10	17	.15		.04			
239.0	243.0	74415	4.0	.0	****	3.44	.06	3.71	9.45	25.60			3	13	17	.18		.01			

DDH: 77018 UTM-N: 9790.4 UTM-E: 14417.4 UTM-ELEV: 3831.1 TOTAL DEPTH: 297.0 SECTION:
 RFE: RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
243.0	247.0	74416	4.0	.0	****	3.51	.05	4.13	11.48	38.30			4	14	19	.14		.02			
247.0	252.0	74417	5.0	.0	****	4.87	.02	1.34	2.38	14.30			1	39	40	.01		.01			
252.0	257.0	74418	5.0	.0	****	3.28	.20	.88	3.76	14.20			9	12	21	.15		.04			
257.0	262.0	74419	5.0	.0	****	3.34	.13	.34	2.64	8.60			9	14	23	.14		.02			
262.0	267.0	74420	5.0	.0	****	3.39	.10	3.11	3.33	43.90			7	14	21	.15		.03			
267.0	272.0	74421	5.0	.0	****	3.33	.11	2.16	5.77	29.50			5	9	15	.22		.04			
272.0	277.0	74422	5.0	.0	****	3.48	.13	.92	6.69	17.10			6	13	20	.13		.06			
277.0	282.0	74423	5.0	.0	****	3.53	.09	1.24	4.81	18.60			4	19	23	.14		.03			
282.0	287.0	74424	5.0	.0	****	3.68	.24	1.28	2.98	17.10			8	18	26	.12		.04			
287.0	292.0	74425	5.0	.0	****	4.28	.43	4.77	3.74	33.80			11	24	35	.04		.07			
292.0	297.0	74426	5.0	.0	****	3.47	.14	1.90	3.33	24.50			5	19	25	.13		.02			

PAGE: 147

```
DDH: 77020      UTM-N: 9925.2      UTM-E: 14437.8      UTM-ELEV: 3866.9      TOTAL DEPTH: 95.0      SECTION:
RFE: RFE DIR: 0 PLUNGE ANGLES: 0      0 DHD CALC: 1 SS CALC: 0
```

[illegible]

DDH: 77021 UTM-N: 9957.9 UTM-E: 14355.8 UTM-ELEV: 3853.0 TOTAL DEPTH: 80.0 SECTION:
 RFE: RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
9.5	13.0	74446	3.5	.0	****	3.26	.04	.92	2.70	9.50			6	14	21	.13		.15			
13.0	16.0	74447	3.0	.0	****	3.48	.02	.84	3.55	8.40			2	25	27	.14		.03			
16.0	21.0	74448	5.0	.0	****	3.77	.03	1.27	4.77	9.50			2	29	31	.11		.02			
21.0	26.0	74449	5.0	.0	2C0	3.25	.06	2.79	4.97	28.60			3	10	14	.20		.02			
26.0	31.0	74450	5.0	.0	****	3.20	.09	2.36	3.50	21.10			4	13	18	.20		.04			
31.0	36.0	74451	5.0	.0	****	3.21	.05	3.43	3.85	31.80			3	10	14	.20		.04			
36.0	41.0	74452	5.0	.0	****	2.98	.07	1.89	4.77	18.80			3	6	10	.27		.02			
41.0	43.5	74453	2.5	.0	****	3.49	.07	1.77	3.73	19.50			4	22	27	.22		.05			
43.5	47.5	74454	4.0	.0	****	4.31	.02	4.98	14.16	34.90			4	22	26	.02		.03			
47.5	50.5	74455	3.0	.0	****	3.05	.07	6.87	15.92	50.20			4	23	28	.02		.04			
50.5	53.5	74456	3.0	.0	****	3.23	.30	1.30	2.90	13.30			6	12	19	.21		.02			
53.5	57.0	74457	3.5	.0	****	3.41	.13	5.06	10.24	51.20			5	14	19	.06		.02			

DDH: 77023 UTM-N: 9877.7 UTM-E: 14682.6 UTM-ELEV: 3839.8 TOTAL DEPTH: 117.0 SECTION:
 RFE: RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS----						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
12.0	16.0	74461	4.0	.0	****	3.23	.14	1.76	5.64	19.90				3	18	21	.11		.03		
16.0	21.0	74462	5.0	.0	****	3.40	.07	2.36	6.90	18.90				3	34	37	.12		.03		
21.0	26.0	74463	5.0	.0	****	3.28	.09	1.51	4.99	19.00				2	14	17	.14		.03		
26.0	31.0	74464	5.0	.0	****	3.16	.11	2.08	6.16	22.50				2	16	19	.09		.04		
31.0	36.0	74465	5.0	.0	****	3.42	.12	1.73	2.48	34.70				2	22	25	.11		.03		
36.0	41.0	74466	5.0	.0	****	3.49	.02	.68	2.97	11.60				1	27	29	.16		.01		
41.0	46.0	74467	5.0	.0	****	3.40	.05	1.36	4.77	17.90				3	17	20	.15		.02		
46.0	51.0	74468	5.0	.0	****	3.35	.04	3.36	7.86	44.60				1	17	18	.19		.01		
51.0	56.0	74469	5.0	.0	****	3.60	.02	3.94	9.20	39.60				1	17	19	.15		.01		
56.0	61.0	74470	5.0	.0	****	3.32	.03	4.01	8.20	41.20				2	14	17	.15		.02		
61.0	75.0	74471	14.0	.0	****	3.10	.02	1.29	5.41	18.10				2	11	14	.15		.01		
75.0	80.0	74472	5.0	.0	****	3.56	.02	.16	.29	6.10				2	23	25	.15		.01		
80.0	85.0	74473	5.0	.0	****	3.10	.02	2.80	4.44	36.40				2	11	14	.20		.01		
85.0	90.0	74474	5.0	.0	****	2.97	.02	2.34	5.89	34.10				3	6	10	.21		.02		
90.0	95.0	74475	5.0	.0	****	3.27	.06	3.84	8.43	40.20				3	9	12	.15		.03		
95.0	100.0	74476	5.0	.0	****	3.33	.03	.87	2.26	14.40				2	17	20	.18		.02		
100.0	105.0	74477	5.0	.0	****	4.78	.03	3.54	7.77	32.60				2	36	39	.03		.03		
105.0	111.0	74478	6.0	.0	****	3.12	.08	7.92	4.46	82.10				5	7	12	.34		.02		
111.0	117.0	74479	6.0	.0	****	3.37	.11	2.88	10.13	37.70				7	13	21	.07		.04		

DDH: 78005 UTM-N: 9282.6 UTM-E: 13918.3 UTM-ELEV: 3748.1 TOTAL DEPTH: 173.0 SECTION:
 RFE: RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %
18.1	20.6	74482	2.5	.0	****	2.97	.35	.76	1.05	10.30			7	8	16	.10		.09		
20.6	23.1	74483	2.5	.0	****	2.97	.06	1.80	4.49	10.30			1	5	6	.10		.02		
23.1	25.6	74484	2.5	.0	****	2.97	.04	1.53	2.70	10.30			1	3	4	.10		.02		
25.6	28.1	74485	2.5	.0	****	2.97	.04	1.39	2.71	10.30				4	4	.10		.02		
28.1	30.6	74486	2.5	.0	****	2.97	.03	1.20	1.98	10.30			1	5	7	.10		.03		
30.6	33.1	74487	2.5	.0	****	2.97	.05	1.93	3.32	10.30			6	3	9	.10		.09		
33.1	35.6	74488	2.5	.0	****	2.97	.20	3.11	3.98	10.30			10	11	21	.10		.16		
35.6	38.1	74489	2.5	.0	****	2.97	.29	3.06	.71	10.30			24	3	28	.10		.37		
38.1	40.6	74490	2.5	.0	****	4.42	.41	3.34	4.11	61.70			17	16	33	1.59		.35		
40.6	43.1	74491	2.5	.0	****	4.42	.36	3.98	5.32	61.70			19	17	36	1.59		.42		
43.1	45.6	74492	2.5	.0	****	4.42	.40	6.24	8.95	61.70			11	22	34	1.59		.30		
45.6	48.1	74493	2.5	.0	****	4.42	.29	5.84	8.97	61.70			14	18	33	1.59		.41		
48.1	50.6	74494	2.5	.0	****	4.42	.13	4.24	5.95	61.70			9	25	35	1.59		.39		
50.6	53.1	74495	2.5	.0	****	4.42	.34	4.55	6.52	61.70			14	17	32	1.59		.52		
53.1	55.6	74496	2.5	.0	****	4.42	.30	4.12	5.24	61.70			10	25	36	1.59		.40		
55.6	58.1	74497	2.5	.0	****	4.42	.25	5.86	7.60	61.70			10	26	36	1.59		.35		
58.1	60.6	74498	2.5	.0	****	4.65	.09	7.71	7.14	65.10			4	31	36	.93		.29		
60.6	63.1	74499	2.5	.0	****	4.65	.14	7.31	8.68	65.10			3	28	32	.93		.24		
63.1	65.6	74500	2.5	.0	****	4.65	.11	5.38	7.99	65.10			3	27	31	.93		.18		
65.6	68.1	74501	2.5	.0	****	4.65	.12	7.01	10.78	65.10			3	27	30	.93		.10		
68.1	70.6	74502	2.5	.0	****	4.65	.09	7.94	10.65	65.10			2	27	30	.93		.08		
70.6	73.1	74503	2.5	.0	****	4.65	.22	6.26	10.35	65.10			3	28	31	.93		.13		
73.1	75.6	74504	2.5	.0	****	4.65	.23	6.50	7.98	65.10			4	29	33	.93		.33		
75.6	78.1	74505	2.5	.0	****	4.65	.20	7.18	8.61	65.10			3	29	33	.93		.21		
78.1	80.6	74506	2.5	.0	****	4.61	.16	5.66	8.22	61.70			3	33	36	.68		.29		
80.6	83.1	74507	2.5	.0	****	4.61	.18	6.31	8.09	61.70			3	27	30	.68		.16		
83.1	85.6	74508	2.5	.0	****	4.61	.19	5.42	7.91	61.70			5	27	32	.68		.24		
85.6	88.1	74509	2.5	.0	****	4.61	.49	5.89	7.21	61.70			4	29	34	.68		.16		
88.1	90.6	74510	2.5	.0	****	4.61	.45	23.50	8.52	61.70			23	14	38	.68		.34		
90.6	93.1	74511	2.5	.0	****	4.61	.25	9.80	10.12	61.70			5	27	32	.68		.36		
93.1	95.6	74512	2.5	.0	****	4.61	.32	6.06	6.44	61.70			6	30	37	.68		.41		
95.6	98.1	74513	2.5	.0	****	4.61	.14	5.45	5.88	61.70			5	32	37	.68		.29		
98.1	100.6	74514	2.5	.0	****	4.05	.15	4.20	4.76	72.00			5	31	36	1.02		.28		
100.6	103.1	74515	2.5	.0	****	4.05	.21	7.33	7.66	72.00			4	28	33	1.02		.21		
103.1	105.6	74516	2.5	.0	****	4.05	.31	4.94	6.28	72.00			5	30	36	1.02		.29		
105.6	108.1	74517	2.5	.0	****	4.05	.28	4.96	7.50	72.00			6	25	31	1.02		.11		
108.1	110.6	74518	2.5	.0	****	4.05	.27	4.06	10.21	72.00			18	7	25	1.02		.11		
110.6	113.1	74519	2.5	.0	****	4.05	.12	1.88	6.98	72.00			5	5	10	1.02		.07		
113.1	115.6	74520	2.5	.0	****	4.05	.05	3.08	4.13	72.00			3	3	6	1.02		.05		
115.6	118.1	74521	2.5	.0	****	4.05	.07	9.00	5.35	72.00			2	4	7	1.02		.04		
118.1	120.6	74522	2.5	.0	****	3.91	.05	1.63	1.80	44.60			2	2	5	.03		.05		
120.6	123.1	74523	2.5	.0	****	3.91	.03	6.62	3.41	44.60			2	1	3	.03		.05		
123.1	125.6	74524	2.5	.0	****	3.91	.01	2.39	2.01	44.60			1		1	.03		.03		
125.6	128.1	74525	2.5	.0	****	3.91	.03	2.72	4.33	44.60			2	1	3	.03		.04		
128.1	130.6	74526	2.5	.0	****	3.91	.34	2.63	5.06	44.60			8	20	29	.03		.09		
130.6	133.1	74527	2.5	.0	****	3.91	.26	5.73	8.49	44.60			33	8	42	.03		.13		
133.1	135.6	74528	2.5	.0	****	3.91	.55	2.76	2.64	44.60			50	2	52	.03		.05		
135.6	138.1	74529	2.5	.0	****	3.91	.52	3.26	3.10	44.60			50	1	52	.03		.04		
138.1	140.6	74530	2.5	.0	****	3.33	.48	3.66	4.12	17.10			39	3	42	.06		.04		
140.6	143.1	74531	2.5	.0	****	3.33	.55	4.23	8.29	17.10			44	2	46	.06		.06		
143.1	145.6	74532	2.5	.0	****	3.33	.29	3.33	13.01	17.10			13	3	17	.06		.21		

DDH: 78005 UTM-N: 9282.6 UTM-E: 13918.3 UTM-ELEV: 3748.1 TOTAL DEPTH: 173.0 SECTION:
 RFE: RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
145.6	148.1	74533	2.5	.0	****	3.33	.06	1.63	7.08	17.10				3	3	6	.06		.12		
148.1	150.6	74534	2.5	.0	****	3.33	.06	.16	.70	17.10				2	3	5	.06		.04		
150.6	153.1	74535	2.5	.0	****	3.33	.05	.03	.06	17.10				2	3	6	.06		.04		
153.1	155.6	74536	2.5	.0	****	3.33	.02	.07	.08	17.10				2	3	5	.06		.04		
155.6	158.1	74537	2.5	.0	****	3.33	.02	.03	.07	17.10				2	2	4	.06		.04		
158.1	160.6	74538	2.5	.0	****	2.79	.08	2.84	4.38	30.90				4	2	7	.10		.09		
160.6	163.1	74539	2.5	.0	****	2.79	.07	2.80	4.64	30.90				3	4	8	.10		.08		
163.1	165.6	74540	2.5	.0	****	2.79	.09	1.68	3.93	30.90				2	3	6	.10		.02		
165.6	168.1	74541	2.5	.0	****	2.79	.09	1.26	2.09	30.90				1	2	3	.10		.01		
168.1	170.6	74542	2.5	.0	****	2.79	.05	1.72	3.88	30.90				1	2	4	.10		.03		
170.6	173.1	74543	2.5	.0	****	2.79	.08	.62	1.06	30.90				2	1	4	.10		.06		

DDH: 78006 UTM-N: 9482.1 UTM-E: 13915.9 UTM-ELEV: 3709.1 TOTAL DEPTH: 59.1 SECTION:
 RFE: RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----						-----ASSAYS-----																
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.	
5.0	8.0	74546	3.0	.0	****	5.18	.37	5.20	5.04	65.10			3	24	28	24.00		.27				
8.0	10.5	74547	2.5	.0	****	5.18	.17	6.93	7.42	65.10			3	16	20	24.00		.37				
10.5	13.0	74548	2.5	.0	****	5.18	.10	5.66	7.13	65.10			2	12	15	24.00		.25				
13.0	16.0	74549	3.0	.0	****	5.18	.29	1.67	1.41	65.10			1	37	38	24.00		.06				
16.0	19.1	74550	3.1	.0	****	5.18	.23	4.04	3.62	65.10			2	33	36	24.00		.13				
19.1	23.2	74551	4.1	.0	****	4.39	.17	1.01	.49	17.10				30	31	.03		.02				
23.2	27.6	74552	4.4	.0	****	4.39	.60	2.22	3.42	17.10			2	37	40	.03		.09				
27.6	29.1	74553	1.5	.0	****	4.39	.37	5.26	7.53	17.10			20	18	39	.03		.09				
29.1	31.6	74554	2.5	.0	****	4.39	.43	3.48	5.32	17.10			5	33	38	.03		.06				
31.6	34.1	74555	2.5	.0	****	4.39	.24	3.06	4.70	17.10			3	34	37	.03		.11				
34.1	36.6	74556	2.5	.0	****	4.39	.32	2.63	4.77	17.10			2	36	38	.03		.07				
36.6	39.1	74557	2.5	.0	****	4.39	.62	4.49	7.09	17.10			20	19	39	.03		.05				
39.1	41.6	74558	2.5	.0	****	3.03	.20	1.45	3.18	27.40			3	3	7	.10		.04				
41.6	44.1	74559	2.5	.0	****	3.03	.14	1.43	3.05	27.40			2	2	5	.10		.03				
44.1	46.6	74560	2.5	.0	****	3.03	.26	2.75	3.80	27.40			5	6	11	.10		.03				
46.6	49.1	74561	2.5	.0	****	3.03	.61	2.17	4.85	27.40			17	7	24	.10		.04				
49.1	51.6	74562	2.5	.0	****	3.03	.25	.77	2.24	27.40			3	5	9	.10		.03				
51.6	54.1	74563	2.5	.0	****	3.03	.23	2.68	6.00	27.40			4	3	8	.10		.09				
54.1	56.6	74564	2.5	.0	****	3.03	.13	2.17	2.62	27.40			1	1	2	.10		.04				
56.6	59.1	74565	2.5	.0	****	3.03	.21	.82	.55	27.40			3	3	7	.10		.03				

DDH: 78022 UTM-N: 9698.7 UTM-E: 14293.1 UTM-ELEV: 3712.6 TOTAL DEPTH: 103.0 SECTION:
 RFE: RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS---						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
8.0	23.0	74568	15.0	.0	****	4.69	.32	1.67	3.04	8.10			3	38	41	.20		.08			
23.0	43.0	74569	20.0	.0	****	4.35	.23	4.93	9.26	12.80			4	26	30	.20		.12			
43.0	63.0	74570	20.0	.0	****	4.87	.14	4.57	8.18	8.40			1	21	23	.17		.02			
63.0	83.0	74571	20.0	.0	****	4.64	.10	1.56	3.44	8.10			2	37	39	.36		.01			
83.0	103.0	74572	20.0	.0	****	3.78	.17	4.06	9.86	25.50			1	36	38	.21		.03			

DDH: 78023 UTM-N: 9496.6 UTM-E: 14311.1 UTM-ELEV: 3712.6 TOTAL DEPTH: 123.0 SECTION:
 RFE: RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
3.0	23.0	74575	20.0	.0	****	4.51	.31	3.39	2.80	26.70				3	29	32	3.07		.12		
23.0	43.0	74576	20.0	.0	****	4.48	.30	2.01	3.60	25.60				4	25	30	.19		.14		
43.0	63.0	74577	20.0	.0	****	4.85	.35	3.05	5.19	13.10				1	33	35	.19		.03		
63.0	83.0	74578	20.0	.0	****	4.64	.33	2.10	4.26	9.60				2	30	33	.20		.07		
83.0	103.0	74579	20.0	.0	****	4.72	.25	2.92	4.74	17.40				5	4	10	.19		.04		
103.0	123.0	74580	20.0	.0	****	4.15	.19	3.78	5.84	28.00				4	8	13	.26		.07		

DDH: 78024 UTM-N: 9684.9 UTM-E: 14494.2 UTM-ELEV: 3723.1 TOTAL DEPTH: 163.0 SECTION:
 RFE: RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
13.0	33.0	74583	20.0	.0	****	4.14	.07	3.85	7.49	12.10			1	28	30	.21		.03			
33.0	53.0	74584	20.0	.0	****	4.20	.07	3.96	7.34	17.10			3	20	23	.19		.05			
53.0	73.0	74585	20.0	.0	****	3.29	.07	.90	1.90	24.30			2	29	31	.31		.01			
73.0	93.0	74586	20.0	.0	****	3.40	.11	.92	1.35	9.30			2	36	39	.27		.03			
93.0	113.0	74587	20.0	.0	****	4.36	.08	2.46	3.82	38.20			1	36	37	.18		.01			
113.0	133.0	74588	20.0	.0	****	4.44	.07	1.38	2.31	12.40			1	5	6	.19		.02			
133.0	153.0	74589	20.0	.0	****	2.72	.11	1.19	1.64	15.60			1	10	12	.37		.03			
153.0	163.0	74590	10.0	.0	****	2.93	.15	1.42	2.52	13.70			3	36	39	.34		.02			

DDH: 78025 UTM-N: 9508.9 UTM-E: 14078.6 UTM-ELEV: 3696.3 TOTAL DEPTH: 86.0 SECTION:
RFE: RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %
11.0	26.0	74593	15.0	.0	****	4.73	.50	3.23	4.82	21.10			1	20	22	.20		.05		
26.0	46.0	74594	20.0	.0	****	3.61	.30	3.08	5.81	29.90			3	35	39	.27		.02		
46.0	66.0	74595	20.0	.0	****	3.34	.31	11.00	2.16	120.00			6	2	8	.24		.06		
66.0	86.0	74596	20.0	.0	****	2.78	.33	.29	.54	19.30			5	15	20	.30		.06		

DDH: 78026 UTM-N: 9700.0 UTM-E: 14100.0 UTM-ELEV: 3711.0 TOTAL DEPTH: 121.0 SECTION:
 RFE: RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
10.0	21.0	74599	11.0	.0	****	4.63	.48	1.79	3.86	8.40			6	33	40	.19		.18			
21.0	41.0	74600	20.0	.0	****	4.40	.36	.58	1.93	21.80			7	29	37	.19		.19			
41.0	61.0	74601	20.0	.0	****	4.60	.52	1.18	2.92	19.60			4	33	38	.19		.10			
61.0	81.0	74602	20.0	.0	****	4.36	.31	4.04	6.56	10.30			2	36	38	.20		.05			
81.0	101.0	74603	20.0	.0	****	4.20	.06	4.10	8.94	4.70			1	38	39	.21		.02			
101.0	121.0	74604	20.0	.0	****	3.62	.16	1.70	3.97	16.20			3	3	6	.23		.02			

DDH: 78027 UTM-N: 9579.2 UTM-E: 13824.2 UTM-ELEV: 3691.3 TOTAL DEPTH: 31.0 SECTION:
RFE: RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

						-----ASSAYS-----															
-----DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu	Pb	Zn	Ag(AA)	Ag(FA)	Au(FA)	Po	Py	TOT	BaO	Hg	Mn	As	Ba	S.G.
FROM	TO						%	%	%	g/mT	g/mT	g/mT	%	%	Fe	%	%	%	%	%	%
6.0	21.0	74607	15.0	.0	****	3.01	.15	2.03	3.56	23.30				3	3	7	.27				.04
21.0	31.0	74608	10.0	.0	****	2.61	.20	1.95	3.55	17.70				5	16	21	.26				.01

DDH: 79-03 UTM-N: 9491.5 UTM-E: 14715.2 UTM-ELEV: 3879.6 TOTAL DEPTH: 516.0 SECTION: 118+000
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

-----DEPTHS-----						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
139.2	140.0	74616	.8	.0	2D09	3.40	.30	2.55	1.69	41.80		.44	10	7	17	.80		.30			
140.0	145.0	74617	5.0	.0	2E46	4.57	.24	6.89	6.43	120.00		.31	16	10	27	1.70		.43			
145.0	150.0	74618	5.0	.0	2E46	4.55	.16	6.76	5.96	111.50		.45	5	18	23	2.00		.38			
150.0	155.0	74619	5.0	.0	2E46	4.68	.11	7.49	7.67	100.50		.72	4	16	20	2.60		.28			
155.0	160.0	74620	5.0	.0	2E46	4.72	.17	7.46	6.41	112.20		.84	8	15	24	2.30		.39			
160.0	165.0	74621	5.0	.0	2E46	4.74	.15	6.39	5.56	90.50		.61	7	18	26	2.00		.46			
165.0	170.0	74622	5.0	.0	2E46	4.58	.13	7.15	5.98	104.10		.64	6	14	20	2.50		.44			
170.0	175.0	74623	5.0	.0	2E46	4.60	.09	3.74	3.90	57.60		.53	3	25	29	1.80		.18			
175.0	180.0	74624	5.0	.0	2G40	4.67	.08	4.70	5.83	34.30		.78	2	22	25	2.10		.12			
180.0	185.0	74625	5.0	.0	2E4	4.78	.02	3.51	5.72	46.70		.23	2	32	34	1.20		.02			
185.0	188.5	74626	3.5	.0	2D4	4.01	.09	3.47	10.30	52.50		.36	3	18	22	1.10		.04			
227.5	230.0	74628	2.5	.0	2D0	4.08	.15	3.36	3.63	29.20		.14	2	28	31			.02			
230.0	235.0	74629	5.0	.0	2D09	4.09	.13	.69	.46	8.60		.09	1	33	34			.01			
235.0	240.0	74630	5.0	.0	2F00	4.43	.24	2.15	3.46	20.60		.08	1	35	37			.01			
240.0	245.0	74631	5.0	.0	2C3	4.54	.27	1.19	1.49	11.00		.06	2	38	41			.10			
245.0	250.0	74632	5.0	.0	2F00	4.46	.18	1.42	1.93	4.50		.05	8	34	42			.36			
250.0	255.0	74633	5.0	.0	2F4	4.61	.15	6.50	9.71	44.90		.04	7	28	35			.30			
255.0	260.0	74634	5.0	.0	2E4	4.70	.16	2.66	4.10	13.00		.03	6	35	42			.19			
260.0	265.0	74635	5.0	.0	2D40	4.36	.17	5.73	8.92	20.60		.18	5	27	32			.10			
265.0	270.0	74636	5.0	.0	2D4	3.80	.11	3.87	3.49	78.60		.93	1	24	26			.03			
270.0	275.0	74637	5.0	.0	2D4	3.78	.11	4.03	8.02	18.20		.37	3	20	23			.03			
275.0	280.0	74638	5.0	.0	2F40	4.16	.12	4.90	8.41	23.70		.38	5	24	30			.18			
280.0	285.0	74639	5.0	.0	2F40	4.08	.16	4.96	9.70	12.70		.12	7	21	28			.28			
285.0	290.0	74640	5.0	.0	2F40	4.03	.19	.36	3.38	2.10		.07	10	22	32			.29			
290.0	295.0	74641	5.0	.0	2C39	3.75	.24	.14	1.20	3.10		.09	7	21	29			.18			
295.0	300.0	74642	5.0	.0	2C39	4.01	.36	.07	1.61	2.10		.07	7	25	33			.18			
300.0	305.0	74643	5.0	.0	2C39	3.77	.62	.06	.97	4.10		.07	7	21	28			.17			
305.0	310.0	74644	5.0	.0	2E09	3.98	.41	.27	1.53	2.10		.05	9	25	35			.25			
310.0	315.0	74645	5.0	.0	2E09	4.11	.25	.13	1.36	2.10		.05	9	26	36			.26			
315.0	320.0	74646	5.0	.0	2C39	4.01	.43	.27	1.68	3.80		.05	6	28	34			.17			
320.0	325.0	74647	5.0	.0	2C39	4.30	.55	.06	.87	3.40		.04	4	34	38			.15			
325.0	330.0	74648	5.0	.0	2E1	4.39	.52	.02	.81	2.40		.05	5	35	40			.15			
330.0	335.0	74649	5.0	.0	2E1	4.27	.18	.02	1.14	1.00		.05	4	34	39			.13			
335.0	340.0	74650	5.0	.0	2E1	4.43	.11	.35	2.41	1.70		.05	4	35	39			.11			
340.0	345.0	74651	5.0	.0	2F4	4.48	.08	4.69	9.12	9.30		.05	3	29	33			.08			
345.0	350.0	74652	5.0	.0	2E4	4.31	.03	7.46	12.10	22.30		.05	2	23	26			.02			
350.0	355.0	74653	5.0	.0	2E4	4.33	.03	5.13	11.00	18.20		.05	3	25	28			.02			
355.0	360.0	74654	5.0	.0	2D0	3.57	.04	1.45	4.64	7.60		.09	3	17	21			.06			
360.0	365.0	74655	5.0	.0	2D05	3.74	.06	.95	3.10	6.90		.07	2	22	25			.02			
365.0	370.0	74656	5.0	.0	2E00	4.70	.02	2.37	4.96	13.40		.07	1	37	38			.01			
370.0	375.0	74657	5.0	.0	2E0	4.89	.01	.94	.66	6.90		.05	4	40	45			.01			
375.0	380.0	74658	5.0	.0	2E0	4.86	.01	.08	.17	.70		.05	3	42	45			.01			
380.0	385.0	74659	5.0	.0	2E0	4.86	.02	.96	1.82	6.90		.05	3	40	44			.01			
385.0	390.0	74660	5.0	.0	2C3	4.51	.05	.78	2.02	17.20		.06	3	36	40			.02			
390.0	395.0	74661	5.0	.0	2C3	3.38	.11	.48	1.65	8.90		.06	3	17	20			.01			
395.0	400.0	74662	5.0	.0	2D0	3.35	.09	2.70	4.22	50.10		.08	3	12	15			.03			
400.0	401.0	74663	1.0	.0	2D0	3.12	.09	2.95	3.26	78.20		.05	4	5	10			.04			

DDH: 80-01 UTM-N: 9136.0 UTM-E: 14402.0 UTM-ELEV: 3905.0 TOTAL DEPTH: 584.0 SECTION: 118+000
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

-----DEPTHS-----						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
371.5	374.5	74670	3.0	.0	2C35	3.51	.37	.20	.92	8.40				8 18	26	.05		.04			
374.5	377.0	74671	2.5	.0	2D5	3.17	.20	2.97	4.63	34.20				4 8	13	.03		.04			
377.0	379.5	74672	2.5	.0	2D5	3.38	.10	1.18	5.11	18.40				2 10	13	.03		.02			
379.5	382.0	74673	2.5	.0	2D45	3.36	.11	2.12	11.10	21.50				1 12	14	.05		.04			
382.0	385.0	74674	3.0	.0	2F0	4.83	.12	3.88	4.66	44.80				2 32	34	.10		.09			
385.0	387.5	74675	2.5	.0	2G48	4.63	.24	6.12	7.19	83.70				4 24	28	9.75		.26			
387.5	390.0	74676	2.5	.0	2G48	4.67	.33	5.34	5.95	76.50				5 25	31	8.07		.29			
390.0	392.5	74677	2.5	.0	2G48	4.65	.31	5.32	6.09	77.80				7 21	29	11.88		.39			
392.5	395.0	74678	2.5	.0	2G48	4.74	.25	5.71	6.92	84.00				4 21	25	18.06		.31			
395.0	397.5	74679	2.5	.0	2G48	4.63	.26	5.43	6.86	82.10				5 21	26	14.31		.34			
397.5	400.0	74680	2.5	.0	2G48	5.03	.27	5.87	6.01	83.40				5 23	29	11.00		.25			
400.0	402.5	74681	2.5	.0	2G48	4.61	.21	5.10	6.45	72.20				4 25	30	8.65		.30			
402.5	405.0	74682	2.5	.0	2G48	4.55	.14	4.39	6.25	51.30				3 27	30	8.69		.28			
405.0	407.5	74683	2.5	.0	2G48	4.83	.03	5.26	6.19	71.90				2 27	30	7.80		.19			
407.5	410.0	74684	2.5	.0	2G48	4.78	.03	4.79	6.23	67.80				2 28	31	5.79		.17			
410.0	412.5	74685	2.5	.0	2G48	4.78	.05	5.69	6.89	78.10				3 27	30	6.15		.13			
412.5	414.0	74686	1.5	.0	2H46	4.42	.37	8.27	7.16	113.50			22	9	31	3.17		.51			
414.0	416.0	74687	2.0	.0	2G48	4.59	.09	6.92	6.52	107.60			9	16	25	16.89		.52			
416.0	418.0	74688	2.0	.0	2G48	4.59	.10	5.75	5.35	86.20			9	20	29	10.41		.53			
418.0	420.5	74689	2.5	.0	2A06	2.85	.05	.52	.59	12.10			2	2	4	5.51		.06			
420.5	423.0	74690	2.5	.0	2A06	2.79	.06	.60	.79	16.20			2	2	5	3.34		.06			
423.0	425.0	80025	2.0	.0	2L14		.01	.03	.01	2.80			1	2	3	3.56		.03			
425.0	427.5	80026	2.5	.0	2L14		.05	.98	1.18	20.53			2	2	5	3.55		.11			
427.5	430.0	80027	2.5	.0	2L14		.07	1.97	2.48	42.30			3	4	7	3.91		.18			
430.0	431.5	80028	1.5	.0	2L14		.11	1.40	1.76	32.97			4	6	10	3.82		.16			
431.5	435.0	80029	3.5	.0	2L14		.04	.56	.86	19.28			4	2	6	4.28		.10			
435.0	437.5	80030	2.5	.0	2L14		.07	1.00	1.78	31.17			4	4	9	6.79		.12			
437.5	440.0	80031	2.5	.0	2A0		.13	.70	1.45	29.86			3	4	8	9.45		.09			
440.0	442.0	80032	2.0	.0	2L14		.15	3.37	3.02	87.81			6	5	12	5.53		.21			
442.0	444.0	80033	2.0	.0	2L14		.18	1.61	1.99	50.39			5	4	10	3.80		.17			
444.0	446.0	80034	2.0	.0	2D4		.18	10.90	6.87	261.26			10	8	18	4.57		.45			
446.0	448.0	80035	2.0	.0	2L14		.08	4.46	1.18	87.71			2	2	4	6.39		.10			
448.0	450.0	74692	2.0	.0	2D69	3.48	.24	2.98	3.54	75.50			5	11	16	7.24		.18			
450.0	453.0	74693	3.0	.0	2H49	4.20	.42	4.76	6.58	93.60			17	18	35	.15		.26			
453.0	457.0	74694	4.0	.0	2D9	2.96	.31	2.29	4.76	59.70			3	4	8	.06		.11			
457.0	460.0	74695	3.0	.0	2H49	4.35	.37	6.35	10.98	90.80			26	7	33	2.69		.12			
460.0	462.5	74696	2.5	.0	2G4	4.55	.11	5.96	7.70	81.50			3	4	8	26.42		.15			
462.5	465.0	74697	2.5	.0	2G4	4.65	.14	5.44	8.84	63.50			2	17	19	25.45		.08			
465.0	467.5	74698	2.5	.0	2F49	5.00	.35	6.43	12.00	54.40			1	29	31	.26		.05			
467.5	470.0	74699	2.5	.0	2F19	5.00	.45	2.11	3.35	26.40			1	31	33	.06		.03			
470.0	472.5	74700	2.5	.0	2E49	4.26	.44	3.52	4.23	33.00			1	34	36	.06		.06			
472.5	475.0	74701	2.5	.0	2E49	4.90	.20	5.58	10.45	42.00			1	31	33	.06		.04			
475.0	477.5	74702	2.5	.0	2E9	4.37	.26	2.07	1.34	14.60			6	31	37	.03		.18			
477.5	480.0	74703	2.5	.0	2E49	4.57	.23	2.39	2.46	20.20			2	35	37	.03		.06			
480.0	482.5	74704	2.5	.0	2E49	4.69	.43	1.90	3.11	23.60			2	35	38	.02		.07			
482.5	485.0	74705	2.5	.0	2E49	4.61	.31	3.09	3.77	26.10			2	33	36	.03		.10			
485.0	487.5	74706	2.5	.0	2E49	4.78	.24	1.88	2.73	19.00			2	35	38	.02		.09			
487.5	492.5	74707	5.0	.0	2E9	4.50	.52	.80	1.72	17.40			6	33	39	.04		.19			
492.5	495.0	74708	2.5	.0	2E9	4.72	.45	.97	1.71	19.20			4	35	39	.01		.13			
495.0	497.5	74709	2.5	.0	2E9	4.78	.51	1.28	2.02	25.80			3	36	40	.01		.13			
497.5	500.0	74710	2.5	.0	2E09	4.61	.13	1.70	1.34	17.10			3	35	38	.01		.10			

DDH: 80-01 UTM-N: 9136.0 UTM-E: 14402.0 UTM-ELEV: 3905.0 TOTAL DEPTH: 584.0 SECTION: 118+000
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

-----DEPTHS-----						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
500.0	502.5	74711	2.5	.0	2E49	4.85	.20	2.38	2.98	21.20			1	36	38	.01		.05			
502.5	505.0	74712	2.5	.0	2E49	4.83	.29	3.48	5.83	33.20			1	34	35	.01		.03			
505.0	507.5	74713	2.5	.0	2F4	4.65	.07	6.50	10.80	45.70			1	30	32	.02		.02			
507.5	510.0	74714	2.5	.0	2F4	4.61	.07	7.53	13.90	57.20			2	28	30	.01		.03			
510.0	514.0	74715	4.0	.0	2F09	4.10	.42	2.22	3.51	17.40			3	28	32	.15		.07			
514.0	518.0	74716	4.0	.0	2F09	4.39	.36	2.43	5.01	21.80			4	29	34	.08		.07			
518.0	524.0	74717	6.0	.0	2F09	4.15	.37	2.95	6.50	24.30			8	23	31	.06		.06			
524.0	526.0	74718	2.0	.0	2B00	2.69	.01	.54	.29	8.10					1	.01		.02			
526.0	528.0	74719	2.0	.0	2B00	2.67	.01	2.40	.53	34.20						.02		.02			
528.0	530.0	74720	2.0	.0	2A4	2.79	.04	.96	4.51	17.70			2		3	.16		.07			
530.0	532.5	74721	2.5	.0	2A4	2.80	.06	1.25	3.84	16.80			2	2	4	.15		.03			
532.5	535.0	74722	2.5	.0	2A4	2.96	.16	1.41	3.06	28.00			3	5	8	.18		.02			
535.0	537.5	74723	2.5	.0	2A00	2.77	.03	.84	2.53	11.80			1	1	3	.21		.02			
537.5	540.0	74724	2.5	.0	2A00	2.76	.02	1.06	2.70	16.80			1		2	.17		.02			
540.0	542.5	74725	2.5	.0	2A00	2.87	.14	1.58	3.52	27.60			3	2	6	.21		.03			
542.5	545.0	74726	2.5	.0	2A0	3.04	.19	.96	1.92	36.00			6	6	13	.14		.04			
545.0	547.5	74727	2.5	.0	2A0	2.77	.08	.96	2.30	15.90			2	2	5	.16		.03			
547.5	550.0	74728	2.5	.0	2A0	2.74	.07	.69	2.52	9.00			3		3	.30		.05			
550.0	552.5	74729	2.5	.0	2A0	2.84	.06	1.04	2.53	14.90			4	1	6	.12		.09			
552.5	555.0	74730	2.5	.0	2A40	2.99	.11	.68	5.99	61.90			3	2	6	.39		.04			
555.0	557.5	74731	2.5	.0	2A40	2.76	.04	.95	2.67	9.90			2	1	4	.20		.05			
557.5	560.0	74732	2.5	.0	2A00	2.79	.05	.63	1.23	13.40			2	1	3	.27		.02			
560.0	562.5	74733	2.5	.0	2A4	2.85	.15	.91	3.18	28.60			3	2	5	.15		.04			
562.5	565.0	74734	2.5	.0	2A4	2.88	.17	.98	3.63	29.20			3	2	5	.20		.04			
565.0	567.5	74735	2.5	.0	2A0	2.96	.29	.32	2.65	18.00			4	6	11	.15		.03			
567.5	570.0	74736	2.5	.0	2A0	3.10	.17	.61	2.42	22.10			5	8	13	.13		.03			
570.0	572.5	74737	2.5	.0	2A4	2.97	.14	.68	3.37	21.80			4	4	8	.17		.03			
572.5	575.0	74738	2.5	.0	2A4	2.87	.14	1.30	2.65	24.90			2	2	5	.12		.03			
575.0	577.5	74739	2.5	.0	2A0	2.84	.14	.97	2.22	25.20			2	2	5	.15		.02			
577.5	580.0	74740	2.5	.0	2A0	2.78	.09	.49	.75	11.20			2	2	4	.33		.02			
580.0	584.0	74741	4.0	.0	2A0	2.76	.10	.90	1.70	14.60			1	1	3	.18		.02			

DDH: 80-02 UTM-N: 8305.7 UTM-E: 14914.5 UTM-ELEV: 4061.2 TOTAL DEPTH: 680.0 SECTION: 125
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
465.0	468.0	74747	3.0	.0	2A0	2.98	.11	.04	.14	2.20			4	7	11	.34		.13			
468.0	471.0	74748	3.0	.0	2C0	3.56	.07	.01	.08	1.89			1	21	22	.04		.02			
471.0	473.5	74749	2.5	.0	2E1	3.62	.08	.35	3.95	4.40			.07	1	21	23	.01	.05			
473.5	476.0	74750	2.5	.0	2E1	3.43	.14	.29	2.83	4.70			.14	1	18	19	.02	.05			
476.0	478.5	74751	2.5	.0	2F4	3.54	.11	3.62	6.34	26.69		5.40	2	17	20	.02		.07			
478.5	481.0	74752	2.5	.0	2F4	3.60	.07	4.41	10.71	33.89			.27	2	14	16	.48	.02			
481.0	483.5	74753	2.5	.0	2F4	3.72	.10	8.89	14.99	71.79			.07	3	8	11	.14	.02			
483.5	486.0	74754	2.5	.0	2G4	4.41	.05	3.99	7.78	42.29			.14	1	13	15	33.95	.05			
486.0	488.5	74755	2.5	.0	2G4	4.67	.08	6.73	7.57	119.99			.07	2	13	16	31.39	.23			
488.5	491.0	74756	2.5	.0	2G74	4.30	.20	3.85	8.58	75.29			.13	9	16	25	11.91	.28			
528.0	531.0	74758	3.0	.0	2H4	3.97	.31	2.95	4.48	49.50			.01	19	17	37	.07	.14			
531.0	533.5	74759	2.5	.0	2H4	4.20	.32	2.72	5.04	45.10			.07	21	19	40	.05	.07			
533.5	536.0	74760	2.5	.0	2H4	4.24	.29	4.02	5.58	64.70			.07	22	18	40	.02	.07			
536.0	538.5	74761	2.5	.0	2H0	4.09	.22	.75	1.25	13.40			.14	13	24	37	.01	.11			
538.5	541.0	74762	2.5	.0	2E4	4.30	.11	1.52	2.83	30.80			.27	6	29	36	.01	.16			
541.0	543.5	74763	2.5	.0	2C7	3.89	.20	.93	.24	26.39				13	15	28	.02	.38			
543.5	546.0	74764	2.5	.0	2C7	3.49	.23	.57	.36	13.09				12	16	28	.01	.46			
546.0	548.5	74765	2.5	.0	2C7	3.47	.23	.38	.34	10.30				10	16	27	.02	.35			
548.5	551.0	74766	2.5	.0	2C7	3.41	.29	.54	.49	10.59				9	15	24	.01	.34			
551.0	553.5	74767	2.5	.0	2C7	3.43	.34	.34	.48	13.99				10	16	26	.01	.41			
553.5	556.5	74768	3.0	.0	2D7	4.13	.40	2.50	4.11	36.39			.69	11	22	34	.01	.40			
556.5	559.5	74769	3.0	.0	2E47	4.25	.39	2.83	4.76	41.70			.14	14	25	39	.01	.34			
559.5	562.5	74770	3.0	.0	2E4	4.33	.20	2.56	3.72	42.00			.07	6	29	35	.01	.24			
562.5	565.0	74771	2.5	.0	2F4	4.74	.10	4.88	6.37	48.79			.07	2	34	36	.01	.05			
565.0	568.0	74772	3.0	.0	2F4	4.75	.05	5.32	8.32	46.00			.01	2	33	35	.01	.05			
568.0	571.0	74773	3.0	.0	2E4	4.51	.14	2.37	5.95	25.80			.01	5	31	36	.02	.11			
571.0	573.5	74774	2.5	.0	2F4	3.91	.17	4.50	6.95	32.29			.07	9	18	27	.02	.19			
573.5	576.0	74775	2.5	.0	2C0	3.18	.14	.39	.53	6.79			.07	5	10	16	.17	.05			
576.0	578.5	74776	2.5	.0	2C0	3.08	.20	.27	.58	4.40			.07	5	8	14	.38	.07			
578.5	581.0	74777	2.5	.0	2D0	3.02	.14	1.53	3.83	15.59			.07	4	4	9	.40	.04			
581.0	583.5	74778	2.5	.0	2D0	3.22	.16	1.71	3.33	19.30			.01	5	9	15	.23	.04			
583.5	586.0	74779	2.5	.0	2D0	3.12	.20	1.29	3.29	19.60			.07	5	7	12	.47	.04			
586.0	588.5	74780	2.5	.0	2D0	3.22	.22	2.64	1.71	37.60			.07	7	8	16	.27	.07			
588.5	591.0	74781	2.5	.0	2C07	3.25	.22	3.35	.10	43.89			.07	10	9	19	.11	.10			
591.0	593.5	74782	2.5	.0	2C0	3.16	.17	.23	.83	6.79			.01	6	9	15	.28	.05			
593.5	596.0	74783	2.5	.0	2H4	4.38	.23	4.21	7.12	45.10			.07	15	19	34	.04	.13			
596.0	600.0	74784	4.0	.0	2F4	4.51	.11	4.61	10.18	33.29			.14	3	26	29	.04	.08			
600.0	606.0	74785	6.0	.0	2F0	4.33	.17	3.60	5.46	34.20			.07	4	26	30	.02	.31			
606.0	610.0	74786	4.0	.0	2F8	4.42	.32	4.04	4.50	47.29			.07	19	16	36	.04	.11			
610.0	613.0	74787	3.0	.0	2D4	3.37	.38	2.49	8.68	82.70			.21	5	6	11	.11	.07			
613.0	615.0	74788	2.0	.0	2D0	3.91	.11	2.27	3.62	25.80			.07	6	21	28	.10	.11			
615.0	618.0	74789	3.0	.0	2D4	4.29	.35	8.22	12.42	87.70			.21	16	13	30	.02	.08			
618.0	621.0	74790	3.0	.0	2D0	3.47	.23	1.02	5.05	19.60			.14	6	14	20	.11	.08			
621.0	623.5	74791	2.5	.0	2D0	4.17	.04	3.22	6.33	30.49			.07	1	25	27	.07	.02			
623.5	626.0	74792	2.5	.0	2A4	2.85	.05	1.29	4.15	12.40			.14		3	4	.40	.01			
626.0	628.5	74793	2.5	.0	2A4	3.08	.11	3.25	7.86	41.39			.41	1	5	7	.16	.01			
628.5	631.0	74794	2.5	.0	2A4	2.24	.05	2.79	9.83	24.89			.27	2	3	6	.14	.02			
631.0	633.5	74795	2.5	.0	2A4	4.15	.05	1.56	5.53	22.69			.34	1	6	7	.14	.02			
633.5	636.0	74796	2.5	.0	2A4	2.99	.07	2.41	5.42	33.60			.41	2	5	8	.16	.02			
636.0	638.5	74797	2.5	.0	2A4	3.24	.19	7.67	5.74	59.70			.27	4	5	9	.13	.02			

DDH: 80-02 UTM-N: 8305.7 UTM-E: 14914.5 UTM-ELEV: 4061.2 TOTAL DEPTH: 680.0 SECTION: 125
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
638.5	641.0	74798	2.5	.0	2A4	2.91	.08	3.24	5.58	33.29		.69	2	3	5	.13		.02			
641.0	643.5	74799	2.5	.0	2A0	2.85	.08	1.47	2.19	19.00		.55	2	4	7	.16		.01			
643.5	646.0	74800	2.5	.0	2A0	2.91	.11	.65	.46	14.30		.41	2	5	7	.14		.02			
646.0	648.5	74801	2.5	.0	2A0	2.98	.13	1.33	2.25	22.10		.55	3	4	8	.13		.04			
648.5	651.0	74802	2.5	.0	2A0	2.77	.08	.36	.59	9.90			3	2	6	.13		.02			
651.0	653.5	74803	2.5	.0	2A0	2.89	.08	.11	.49	3.39			2	3	6	.14		.02			
653.5	656.0	74804	2.5	.0	2A0	2.93	.10	.28	.65	5.90			3	6	9	.16		.02			
656.0	658.5	74805	2.5	.0	2A0	2.89	.14	.28	.36	6.79			3	3	6	.14		.02			
658.5	661.0	74806	2.5	.0	2A0	2.75	.11	.20	.33	6.50			1	1	3	.34		.02			
661.0	663.5	74807	2.5	.0	2A0	2.74	.05	.58	1.47	13.99			1	1	3	.20		.02			
663.5	666.0	74808	2.5	.0	2A4	3.58	.07	1.23	3.83	18.00		.14	1	1	3	.14		.04			
666.0	668.5	74809	2.5	.0	2A4	2.19	.05	1.62	4.69	22.69		.14	1		2	.11		.02			
668.5	671.0	74810	2.5	.0	2A4	2.68	.08	1.68	3.06	34.20		.21	1		2	.14		.01			
671.0	673.5	74811	2.5	.0	2A0	2.83	.17	.84	.72	21.80			3	4	7	.14		.02			
673.5	676.0	74812	2.5	.0	2A0	2.87	.14	.28	.65	19.30			3	3	6	.14		.02			
676.0	678.5	74813	2.5	.0	2A0	2.83	.22	.39	.40	33.00			3	4	8	.17		.02			

DDH: 80-03 UTM-N: 8299.4 UTM-E: 15116.6 UTM-ELEV: 4086.3 TOTAL DEPTH: 663.0 SECTION: 126
 RFE: S2 RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
421.0	423.5	74818	2.5	.0	2C6	3.18	.27	.34		12.80			3	13	17	.27					.08
423.5	426.0	74819	2.5	.0	2C6	2.96	.13	.12		5.60			1	8	10	.29					.05
426.0	428.5	74820	2.5	.0	2C6	3.26	.16	.43	.47	9.30			2	16	19	.13					.12
428.5	431.0	74821	2.5	.0	2C6	3.38	.07	.14	.24	13.40				20	21	.10					.03
431.0	433.5	74822	2.5	.0	2C6	3.46	.09	.11	.40	7.80			2	21	23	.06					.05
433.5	436.0	74823	2.5	.0	2C6	3.69	.17	.52	.43	10.00			5	24	29	.05					.18
436.0	438.5	74824	2.5	.0	2C6	3.39	.13	.35	.34	10.60			2	20	22	.10					.07
438.5	440.0	74825	1.5	.0	2C6	3.93	.16	.18	.28	13.40				28	29	.10					.02
440.0	442.5	74826	2.5	.0	2A0	3.38	.13	.14	.15	12.40				19	20	.13					.02
442.5	445.0	74827	2.5	.0	2A0	3.38	.22	.12	.09	7.20			1	19	21	.10					.02
445.0	447.5	74828	2.5	.0	2C6	3.66	.18	.10	.20	6.80			2	24	26	.07					.05
447.5	450.0	74829	2.5	.0	2D4	3.59	.11	4.65	7.98	37.60		.14	2	16	18	.15					.06
450.0	452.5	74830	2.5	.0	2D4	4.64	.04	4.93	8.56	42.90		.01	1	24	26	16.41					.03
452.5	455.0	74831	2.5	.0	2D4	4.73	.03	4.20	6.93	44.80		.07		30	31	10.58					
455.0	457.5	74832	2.5	.0	2F4	4.71	.03	5.90	8.88	64.10		.07	1	33	35	.32					.02
457.5	460.0	74833	2.5	.0	2F4	4.49	.27	6.43	8.90	75.30		.07	1	30	32	.53					.03
460.0	462.0	74834	2.0	.0	2EC	4.17	.22	.78	1.99	10.90		.07		34	35	.08					.04
462.0	464.0	74835	2.0	.0	2EC	4.18	.05	.40	1.60	9.00				31	32	.09					.05
464.0	467.0	74836	3.0	.0	2C5	3.14	.10	.29	.84	5.60			1	14	16	.44					.07
467.0	469.0	74837	2.0	.0	1D4	2.89	.13	.15	.10	5.30			2	3	6	1.16					.11
469.0	471.0	74838	2.0	.0	2C5	3.22	.09	.48	.57	8.40			1	15	17	.39					.08
471.0	473.0	74839	2.0	.0	2F4	4.45	.16	5.29	7.35	82.70		.27	4	26	31	.50					.13
505.0	508.0	74841	3.0	.0	2E4	4.08	.09	3.20	4.60	76.80		.07	2	27	30	.87					.15
508.0	511.0	74842	3.0	.0	2E4	3.71	.17	4.51	1.04	124.70		.27	10	17	28	.22					.21
511.0	514.0	74843	3.0	.0	2E7	4.35	.41	1.02	.52	32.00		.14	21	21	42	.07					.23
514.0	516.0	74844	2.0	.0	1D4	3.25	.25	3.80	.74	136.50		.75	9	12	21	.26					.18
516.0	518.0	74845	2.0	.0	2CE	3.46	.20	1.50	.33	47.60				12	13	25	.08				.13
518.0	520.0	74846	2.0	.0	2CE	3.37	.35	.52	.27	24.60				12	12	25	.06				.16
520.0	522.5	74847	2.5	.0	2E74	4.38	.09	4.21	2.09	111.30		.55	11	27	39	.07					.13
522.5	525.0	74848	2.5	.0	2E0	4.61	.09	1.42	.76	20.50			2	36	39	.05					.10
525.0	527.5	74849	2.5	.0	2E0	4.58	.20	1.03	.51	13.70			3	37	40	.05					.15
527.5	530.0	74850	2.5	.0	2F0	4.41	.12	1.50	.98	15.90			3	36	39	.05					.12
530.0	532.5	74851	2.5	.0	2E0	4.60	.17	1.92	1.43	24.30		.01	5	34	39	.06					.18
532.5	535.0	74852	2.5	.0	2E4	4.79	.34	3.25	2.69	39.20			5	34	39	.06					.23
535.0	537.5	74853	2.5	.0	2E0	4.43	.15	2.81	1.26	36.40		.07	2	36	38	.04					.07
537.5	540.0	74854	2.5	.0	2E0	3.38	.20	2.20	1.29	25.80		.14	4	32	36	.05					.17
540.0	542.5	74855	2.5	.0	2E4	4.88	.24	4.01	4.59	54.10			7	31	38	.06					.38
542.5	545.0	74856	2.5	.0	2E0	4.63	.39	1.67	2.10	28.00		.07	6	34	41	.06					.30
545.0	547.5	74857	2.5	.0	2E4	4.60	.26	2.43	2.16	35.50		.14	6	32	39	.05					.37
547.5	550.0	74858	2.5	.0	2E4	4.24	.24	2.00	2.74	36.40		.14	8	28	36	.04					.44
550.0	552.5	74859	2.5	.0	2E1	4.05	.14	1.80	1.48	23.00		.07	6	27	34	.05					.28
552.5	555.0	74860	2.5	.0	2E1	4.41	.09	.36	.29	11.20			2	35	38	.05					.03
555.0	557.5	74861	2.5	.0	2E1	4.25	.20	.38	.27	13.70			5	30	36	.04					.08
557.5	560.0	74862	2.5	.0	2E1	4.10	.25	.43	.43	13.10			4	31	35	.05					.04
560.0	562.5	74863	2.5	.0	2E4	4.20	.25	3.08	2.47	52.60		.14	7	26	33	.06					.13
562.5	565.0	74864	2.5	.0	2E4	4.30	.28	3.00	5.00	51.60		.07	8	27	36	.08					.27
565.0	567.5	74865	2.5	.0	2E0	4.33	.13	1.77	2.21	22.10		.14	4	32	36	.10					.12
567.5	570.0	74866	2.5	.0	2E4	4.14	.19	2.23	3.73	25.20			5	34	39	.12					.22
570.0	572.5	74867	2.5	.0	2E4	4.34	.24	2.46	3.31	19.90		.07	6	29	36	.05					.37
572.5	575.0	74868	2.5	.0	2E4	4.36	.18	3.00	7.09	32.30		.21	4	30	34	.05					.18

DDH: 80-03 UTM-N: 8299.4 UTM-E: 15116.6 UTM-ELEV: 4086.3 TOTAL DEPTH: 663.0 SECTION: 126
 RFE: S2 RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
575.0	577.5	74869	2.5	.0	2E4	4.59	.22	5.15	6.08	31.40		.14	3	31	35	.04		.14			
577.5	582.5	74870	5.0	.0	2E4	4.30	.18	2.35	3.42	10.60		.07	5	28	33	.05		.23			
582.5	585.0	74871	2.5	.0	2E4	4.07	.12	1.86	2.84	21.80		.01	4	28	32	.04		.17			
585.0	587.5	74872	2.5	.0	2F0	4.91	.03	2.73	6.32	25.80		.07		38	38	.04		.04			
587.5	590.0	74873	2.5	.0	2F4	4.60	.04	4.39	7.93	28.00		.01	1	34	36	.05		.04			
590.0	595.0	74874	5.0	.0	2F4	4.56	.07	3.44	7.49	21.20		.07	1	33	35	.05		.06			
595.0	600.0	74875	5.0	.0	2F4	5.04	.04	2.88	6.63	17.40		.01	1	38	39	.04		.02			
600.0	602.5	74876	2.5	.0	2C0	3.07	.11	.58	1.95	6.20			5	8	14	.33		.06			
602.5	605.0	74877	2.5	.0	2D0	3.23	.16	1.64	4.88	21.20		.14	6	9	16	.15		.10			

DDH: 80-04 UTM-N: 8513.9 UTM-E: 15126.1 UTM-ELEV: 4109.2 TOTAL DEPTH: 704.0 SECTION: 125
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----		-----ASSAYS-----																			
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
582.5	585.0	74883	2.5	.0	2F6	4.53	.04	4.43	7.47	69.00		.07	2	25	27	8.72		.05			
610.5	613.0	74886	2.5	.0	2E84	4.43	.13	3.64	3.45	47.00		.21	6	28	35	.18		.24			
613.0	615.5	74887	2.5	.0	2E4	4.57	.08	2.57	2.69	21.80		.07	2	36	38	.10		.06			
615.5	618.0	74888	2.5	.0	2E0	4.18	.03	.87	.55	7.20		.07		36	37	.11		.01			
618.0	620.5	74889	2.5	.0	2E4	4.34	.07	1.59	2.51	11.20		.07	1	35	36	.10		.01			
620.5	624.0	74890	3.5	.0	2A0	3.98	.01	.44	.80	3.70			1	31	33	.05		.01			
624.0	628.0	74891	4.0	.0	2EC	3.79	.02	1.30	2.38	6.80		.07	1	27	28	.10		.03			
628.0	630.5	74892	2.5	.0	2ED	3.43	.18	1.39	3.50	11.20			4	15	20	.18		.14			
630.5	633.0	74893	2.5	.0	2ED	4.04	.18	3.13	6.83	10.00			5	23	28	.12		.10			
633.0	635.5	74894	2.5	.0	2ED	3.91	.24	3.87	9.44	12.10			6	17	24	.08		.08			
635.5	638.0	74895	2.5	.0	2A1	2.96	.11	.87	3.05	10.90		.14	3	4	8	.28		.03			
638.0	641.5	74896	3.5	.0	2A1	2.90	.06	1.10	2.06	12.40		.14	2	3	5	.31		.03			
641.5	645.0	74897	3.5	.0	2A1	2.77	.05	.82	1.84	10.30		.07	2	1	3	.34		.03			
645.0	648.5	74898	3.5	.0	2A1	2.74	.05	.74	1.81	8.70		.14	1	1	2	.33		.03			
648.5	651.0	74899	2.5	.0	2C5	2.95	.21	2.56	1.08	37.90		.41	3	4	8	.45		.03			
651.0	653.5	74900	2.5	.0	2C5	2.89	.13	1.00	1.16	9.60			6	4	11	.24		.08			
653.5	656.0	74901	2.5	.0	2C5	2.92	.17	.74	.89	8.10			5	3	8	.30		.07			
656.0	658.5	74902	2.5	.0	2C5	3.02	.20	.54	1.43	6.80			6	5	12	.24		.06			
658.5	661.0	74903	2.5	.0	2D4	3.48	.27	4.51	9.86	43.50		.07	7	9	17	.12		.04			
661.0	663.5	74904	2.5	.0	2A1	2.88	.13	1.20	.84	24.30			3	5	8	.24					
663.5	666.0	74905	2.5	.0	2A1	2.77	.09	.33	.64	10.30			2	2	4	.27		.02			
666.0	668.5	74906	2.5	.0	2A1	2.83	.14	.29	.89	15.60			2	3	5	.24		.04			
668.5	671.0	74907	2.5	.0	2A1	2.81	.10	.51	.79	16.80			1	3	5	.19		.04			

DDH: 80-05 UTM-N: 8701.0 UTM-E: 14305.3 UTM-ELEV: 3955.0 TOTAL DEPTH: 589.0 SECTION: 120+000
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %
446.0	449.0	74911	3.0	.0	2C0	2.99	.18	.37	3.42	12.10			6	12	18	.03		.09		
449.0	452.0	74912	3.0	.0	2D0	3.31	.15	2.93	6.89	44.50			7	11	19	.01		.17		
452.0	455.0	74913	3.0	.0	2F49	4.25	.26	5.67	8.32	81.80			9	24	34	.03		.24		
455.0	457.5	74914	2.5	.0	2F4	4.60	.10	8.62	10.27	103.30			3	23	27	6.60		.10		
457.5	460.0	74915	2.5	.0	2G4	4.59	.16	7.48	8.41	98.00			2	18	21	19.46		.09		
460.0	462.5	74916	2.5	.0	2G4	5.47	.16	6.67	7.99	90.50			2	18	21	19.44		.12		
462.5	465.0	74917	2.5	.0	2G4	4.64	.14	6.60	7.93	78.10			2	16	18	23.35		.11		
465.0	467.5	74918	2.5	.0	2F4	4.68	.17	9.81	10.50	112.00			2	28	30	.06		.04		
467.5	470.0	74919	2.5	.0	2G4	4.38	.15	7.88	8.75	90.50			2	17	19	20.17		.09		
470.0	472.5	74920	2.5	.0	2F4	4.78	.17	6.52	7.99	74.30			2	29	32	4.58		.09		
472.5	475.0	74921	2.5	.0	2F4	4.14	.16	7.25	9.80	82.70			3	24	28	.59		.07		
475.0	477.5	74922	2.5	.0	2F49	5.11	.21	7.89	10.20	89.30			4	26	30	3.40		.10		
477.5	480.0	74923	2.5	.0	2F4	4.76	.19	6.25	7.59	69.40			4	30	34	2.44		.19		
480.0	484.0	74924	4.0	.0	2F4	4.90	.08	6.45	9.43	56.90			1	31	33	.01		.03		
484.0	487.5	74925	3.5	.0	2F4	5.64	.13	9.22	8.92	81.80			5	27	32	.03		.13		
487.5	490.5	74926	3.0	.0	2F46	4.92	.19	7.45	7.26	79.30			4	24	29	8.69		.11		
490.5	493.5	74927	3.0	.0	2F49	5.78	.21	7.61	9.03	79.30			7	26	33	.41		.14		
493.5	496.5	74928	3.0	.0	2H49	4.30	.51	5.05	7.75	92.70			28	11	40	.10		.07		
496.5	499.0	74929	2.5	.0	2A4	3.28	.16	2.32	4.52	35.80			6	8	14	.43		.04		
499.0	501.5	74930	2.5	.0	2A4	3.09	.09	1.41	3.43	25.50			4	3	8	.31		.03		
501.5	504.0	74931	2.5	.0	2A0	3.15	.08	.79	2.11	17.10			3	4	7	.29		.02		
504.0	506.5	74932	2.5	.0	2A0	2.97	.07	.60	1.39	15.20			3	4	7	.24		.02		
506.5	509.0	74933	2.5	.0	2A0	2.88	.04	.83	1.67	21.50			2	2	4	.24		.03		
509.0	511.5	74934	2.5	.0	2A0	2.95	.06	1.02	2.14	23.30			3	3	6	.22		.03		
511.5	514.0	74935	2.5	.0	2A4	3.36	.07	3.06	5.40	57.90			4	3	7	.29		.05		
514.0	516.5	74936	2.5	.0	2A4	3.21	.07	1.95	3.25	42.90			5	4	9	.38		.07		
516.5	519.0	74937	2.5	.0	2A0	3.04	.13	1.00	1.41	27.40			4	5	9	.41		.02		
519.0	521.5	74938	2.5	.0	2A4	3.10	.11	1.71	2.98	40.10			5	6	11	.22		.03		
521.5	524.0	74939	2.5	.0	2A0	3.11	.10	1.44	2.14	31.70			3	2	6	.43		.01		
524.0	526.5	74940	2.5	.0	2D5	3.25	.13	1.54	3.19	50.10			5	10	16	.29		.01		
526.5	529.0	74941	2.5	.0	2D5	3.09	.16	1.70	4.47	47.60			4	5	10	.36		.02		
529.0	531.5	74942	2.5	.0	2D59	3.11	.20	1.75	5.09	67.20			5	6	11	.27		.03		
531.5	534.0	74943	2.5	.0	2D5	3.09	.19	2.23	4.43	87.10			5	7	12	.29		.04		
534.0	536.5	74944	2.5	.0	2D5	3.19	.14	2.51	4.82	84.30			5	5	11	.20		.08		
536.5	539.0	74945	2.5	.0	2C5	2.93	.09	1.03	1.70	24.30			3	4	7	.27		.03		

DDH: 80-06 UTM-N: 8859.7 UTM-E: 14928.0 UTM-ELEV: 4027.5 TOTAL DEPTH: 753.0 SECTION: 122+020
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

-----DEPTHS-----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
459.0	461.5	74950	2.5	.0	2E41	4.22	.08	3.61	7.69	64.70				3 23	27	3.28		.06			
461.5	463.5	74951	2.0	.0	2E41	4.69	.08	3.00	4.08	50.40				7 25	33	4.20		.08			
478.5	481.5	74953	3.0	.0	2H9	4.37	.51	4.22	2.51	93.60				21 11	33	.69		.25			
481.5	484.5	74954	3.0	.0	2E41	4.00	.19	3.98	3.33	66.20				5 27	33	3.63		.26			
484.5	488.5	74955	4.0	.0	2G4	4.07	.14	4.71	4.85	79.60				2 23	26	11.06		.15			
488.5	492.5	74956	4.0	.0	2E4	4.26	.17	4.28	3.93	47.60				1 32	34	2.84		.08			
492.5	495.0	74957	2.5	.0	2C3	3.54	.01	.17	.05	6.20					28 28	.02		.06			
495.0	497.0	74958	2.0	.0	2C3	3.86	.01	.16	.06	7.80					32 32	.02		.01			
497.0	499.0	74959	2.0	.0	2E1	4.63	.02	.40	.20	8.70					37 38	.01		.02			
499.0	501.5	74960	2.5	.0	2E1	3.96	.09	.69	.62	9.30				1 32	34	.01		.04			
501.5	504.0	74961	2.5	.0	2E4	4.28	.19	2.65	2.56	26.40				4 28	33	.06		.23			
504.0	506.5	74962	2.5	.0	2E1	4.15	.12	1.08	1.61	13.70				3 30	33	.34		.12			
506.5	509.0	74963	2.5	.0	2E1	4.32	.10	.88	.47	19.60				1 33	35	.42		.04			
509.0	512.5	74964	3.5	.0	2G9	4.75	.24	2.51	4.66	31.40				1 26	27	15.80		.04			
512.5	515.0	74965	2.5	.0	2E69	4.63	.21	1.61	2.89	22.40				2 29	32	5.84		.11			
515.0	517.5	74966	2.5	.0	2G0	4.43	.10	2.34	4.16	27.70				1 20	22	18.26		.08			
517.5	520.0	74967	2.5	.0	2G0	4.73	.15	2.59	4.71	29.90				2 25	27	12.67		.14			
520.0	522.5	74968	2.5	.0	2G0	4.41	.06	2.06	6.85	23.30					11 12	40.84		.03			
522.5	525.0	74969	2.5	.0	2G4	4.51	.16	3.64	6.01	44.80				2 16	18	29.87		.16			
525.0	527.5	74970	2.5	.0	2E6	4.53	.04	1.32	1.92	25.20					34 35	3.12		.02			
527.5	530.0	74971	2.5	.0	2G0	4.60	.07	3.56	5.71	41.70				1 24	26	15.80		.07			
530.0	532.5	74972	2.5	.0	2E48	4.35	.35	3.72	3.10	42.60				4 33	38	.24		.17			
532.5	535.0	74973	2.5	.0	2E1	4.57	.19	1.80	1.71	23.60				1 38	39	.02		.05			
535.0	540.0	74974	5.0	.0	2E41	4.74	.09	3.25	2.54	37.60				1 38	40	.04		.04			
540.0	542.5	74975	2.5	.0	2E1	4.40	.02	.22	.10	9.30					38 39	.01					
542.5	545.0	74976	2.5	.0	2E1	4.51	.03	.16	.09	8.40					39 39	.02		.01			
545.0	547.5	74977	2.5	.0	2E1	4.38	.06	.30	.16	10.60					40 41	.01		.01			
547.5	550.0	74978	2.5	.0	2E41	4.88	.14	2.19	2.27	29.20					35 36	2.29		.04			
550.0	552.5	74979	2.5	.0	2E41	4.90	.09	1.76	2.46	23.30					40 41	.02		.01			
552.5	555.0	74980	2.5	.0	2E1	4.30	.14	.88	.48	19.90					37 37	.04		.01			
555.0	557.5	74981	2.5	.0	2E1	4.70	.06	1.13	.34	24.60					37 38			.01			
557.5	560.0	74982	2.5	.0	2E41	5.11	.06	6.50	4.70	71.80				1 36	37	.01		.05			
560.0	562.5	74983	2.5	.0	2E41	5.23	.07	4.53	2.61	39.20					39 40	.01		.03			
562.5	565.0	74984	2.5	.0	2E1	4.42	.05	1.46	.88	15.60					38 39	.01		.01			
565.0	567.5	74985	2.5	.0	2E1	4.30	.10	1.09	1.28	15.90					37 38	.01		.02			
567.5	570.0	74986	2.5	.0	2E48	4.97	.37	6.38	5.31	95.80				5 31	37	.73		.29			
570.0	572.5	74987	2.5	.0	2E49	4.74	.33	3.48	4.23	47.60				5 34	39	.24		.26			
572.5	575.0	74988	2.5	.0	2E4	4.80	.12	3.48	2.64	40.70				2 36	38			.07			
575.0	577.5	74989	2.5	.0	2E49	4.54	.40	3.89	1.37	80.20				2 33	35	.04		.05			
577.5	580.0	74990	2.5	.0	2E1	4.16	.19	1.54	2.37	27.70				1 33	34	.03		.02			
580.0	582.5	74991	2.5	.0	2E1	4.58	.13	.54	.92	15.90				1 39	40			.02			
585.0	587.5	74993	2.5	.0	2E1	4.64	.07	1.36	1.10	22.40					36 37			.01			
587.5	591.0	74994	3.5	.0	2E1	4.76	.04	.44	.14	13.70					5 6			.02			
591.0	593.5	74995	2.5	.0	2C39	3.89	.26	.40	.48	54.70					28 29	.01		.01			
593.5	596.0	74996	2.5	.0	2E1	4.49	.05	.25	.21	14.30					35 35	.01		.01			
596.0	598.0	74997	2.0	.0	2E4	5.07	.02	3.42	3.33	28.30					36 36	.01		.01			
598.0	601.0	74998	3.0	.0	2E41	3.40	.08	2.37	7.00	37.00					17 18	.03		.02			
601.0	603.5	74999	2.5	.0	2E1	4.74	.18	.87	1.18	14.00					36 37	.02		.01			
603.5	606.0	75000	2.5	.0	2E41	4.04	.15	1.67	2.78	16.80				1 29	30	.04		.03			

DDH: 80-06 UTM-N: 8859.7 UTM-E: 14928.0 UTM-ELEV: 4027.5 TOTAL DEPTH: 753.0 SECTION: 122+020
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

-----DEPTHS-----						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
606.0	608.5	75001	2.5	.0	2E19	4.58	.38	1.74	2.15	17.70				4 30	34			.11			
608.5	611.0	75002	2.5	.0	2E1	3.83	.14	.85	1.01	22.70				1 29	30	.02		.02			
611.0	613.0	75003	2.0	.0	2E19	3.96	.26	.40	1.36	15.60				2 26	29	.03		.09			
613.0	616.0	75004	3.0	.0	2E89	4.30	.33	.33	1.97	7.80				9 27	36			.44			
616.0	619.0	75005	3.0	.0	2E48	4.30	.28	1.45	3.04	10.30				8 28	36	.01		.33			
619.0	621.5	75006	2.5	.0	2F49	4.46	.39	3.33	7.82	19.00				6 26	32	.02		.24			
621.5	624.0	75007	2.5	.0	2F49	4.35	.26	4.58	7.67	20.80				5 37	42	.03		.18			
624.0	626.5	75008	2.5	.0	2F4	4.70	.14	3.60	8.75	22.70				3 29	33	.01		.10			
626.5	629.0	75009	2.5	.0	2F9	4.43	.37	1.96	4.39	15.60				4 28	33	.01		.16			
629.0	631.5	75010	2.5	.0	2F4	4.80	.05	5.16	8.69	48.50				2 31	33	.01		.05			
631.5	634.0	75011	2.5	.0	2F4	4.90	.06	5.72	10.71	28.90				3 27	31			.06			
634.0	636.5	75012	2.5	.0	2F49	4.12	.26	5.73	12.20	34.20				5 20	25	.01		.09			
636.5	639.0	75013	2.5	.0	2F4	4.97	.05	4.87	10.07	28.60				2 31	33	.01		.03			
639.0	641.5	75014	2.5	.0	2F4	4.73	.06	7.30	12.40	42.30				2 28	31	.01		.03			
641.5	644.0	75015	2.5	.0	2F4	4.76	.05	6.86	10.50	39.50				1 31	33			.02			
644.0	646.5	75016	2.5	.0	2F4	5.00	.03	6.83	10.50	39.50				1 31	33	.01		.02			
646.5	649.0	75017	2.5	.0	2F4	4.80	.01	8.37	14.90	45.70				1 27	29	.01		.02			
649.0	651.5	75018	2.5	.0	2D5	3.48	.12	1.26	3.52	27.40				1 19	21	.03		.02			
651.5	654.0	75019	2.5	.0	2D5	3.49	.06	.87	3.52	16.50				1 16	17	.06		.01			
654.0	656.5	75020	2.5	.0	2D45	3.32	.17	4.86	7.07	44.80				2 12	15	.06		.02			
656.5	659.0	75021	2.5	.0	2C5	3.49	.04	.21	2.29	13.40				1 17	19	.06		.02			
659.0	661.5	75022	2.5	.0	2C5	3.55	.03	.40	2.98	20.50				1 20	22	.06		.01			
661.5	664.0	75023	2.5	.0	2D5	3.54	.02	1.42	3.95	16.50				1 18	19	.04		.01			
664.0	666.5	75024	2.5	.0	2D4	3.28	.04	7.18	2.82	55.10				1 20	21	.08		.01			
666.5	669.0	75025	2.5	.0	2D4	3.27	.08	6.32	14.05	32.00				2 8	10	.06		.01			
669.0	671.5	75026	2.5	.0	2D4	3.49	.03	8.20	16.00	36.70				2 8	10	.07		.01			
671.5	674.0	75027	2.5	.0	2D4	3.61	.02	9.60	16.37	36.70				2 9	12	.06		.01			
674.0	676.5	75028	2.5	.0	2D4	3.69	.03	10.15	18.26	39.80				2 9	11	.06		.01			
676.5	679.0	75029	2.5	.0	2D4	3.43	.03	5.15	16.21	25.20				2 9	11	.06		.01			
679.0	681.5	75030	2.5	.0	2D4	3.49	.02	10.20	17.22	41.40				2 8	11	.07		.01			
681.5	684.0	75031	2.5	.0	2D4	3.31	.03	6.04	15.18	24.60				2 6	8	.11		.01			
684.0	686.5	75032	2.5	.0	2D4	3.68	.04	10.63	18.79	33.30				3 7	10	.07		.02			
686.5	689.0	75033	2.5	.0	2D4	3.81	.02	7.33	15.98	23.90				2 12	15	.04		.01			
689.0	691.5	75034	2.5	.0	2D4	3.53	.04	6.40	14.95	20.50				2 11	13	.06		.01			
691.5	694.0	75035	2.5	.0	2D4	3.80	.02	7.42	15.92	28.30				2 13	15	.03		.01			
694.0	696.5	75036	2.5	.0	2D4	3.50	.02	5.74	14.05	21.20				2 11	13	.08		.01			
696.5	699.0	75037	2.5	.0	2D4	3.41	.17	6.46	13.96	33.00				4 8	12	.10		.03			
699.0	701.5	75038	2.5	.0	2D4	5.87	.10	5.14	13.03	32.70				3 13	16	.08		.05			
701.5	704.0	75039	2.5	.0	2D0	3.20	.07	.78	7.72	44.80				2 11	14	.10		.05			
704.0	706.5	75040	2.5	.0	2D4	3.32	.12	4.37	6.86	36.40				6 15	21	.07		.07			
706.5	709.0	75041	2.5	.0	2D4	3.15	.16	3.95	8.65	29.90				5 6	11	.09		.09			
709.0	711.5	75042	2.5	.0	2A0	2.96	.19	.70	2.54	14.30				6 4	10	.18		.05			
711.5	714.6	75043	3.1	.0	2B0	2.95	.14	.35	.15	13.10				1 3	5	.01		.01			
714.6	717.8	75044	3.2	.0	2B4*	3.05	.11	7.63	3.04	114.10				2 2	5	.03		.11			
717.8	721.0	75045	3.2	.0	2B4*	3.13	.16	3.87	12.10	24.90				5 3	8	.07		.13			
721.0	723.5	75046	2.5	.0	2D47	3.50	.40	4.66	13.73	28.00				13 2	15	.08		.08			
723.5	726.0	75047	2.5	.0	2D47	3.36	.34	2.29	10.72	19.90				13 4	17	.06		.09			
726.0	728.0	75048	2.0	.0	2D79	3.40	.27	1.89	4.64	26.70				19 2	22	.07		.11			

DDH: 80-07 UTM-N: 8674.8 UTM-E: 14718.2 UTM-ELEV: 4031.2 TOTAL DEPTH: 699.0 SECTION: 122+020
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

-----DEPTHS-----		-----ASSAYS-----																			
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
451.0	453.0	75054	2.0	.0	2C39	3.18	.21	.25	.07	2.80			9	11	21	.54		.06			
453.0	455.0	75055	2.0	.0	2C39	3.86	.29	.36	.12	13.40			19	16	35	.14		.14			
455.0	457.5	75056	2.5	.0	2F49	4.45	.22	7.79	6.31	127.20			9	21	31	.19		.77			
457.5	460.0	75057	2.5	.0	2F4	4.44	.14	8.42	8.15	133.70			7	22	29	.55		.53			
474.0	477.0	75059	3.0	.0	2H9	4.27	.34	2.37	1.70	71.20			31	9	41	.18		.33			
477.0	480.0	75060	3.0	.0	2G0	2.87	.04	.11	.30	5.60			2	2	5	11.24		.05			
480.0	483.0	75061	3.0	.0	2G0	3.06	.05	.78	1.33	14.90			3	2	5	23.20		.10			
483.0	486.5	75062	3.5	.0	2G0	3.60	.35	3.45	3.76	66.60			6	8	15	18.81		.19			
486.5	489.0	75063	2.5	.0	2H49	4.41	.26	7.76	7.70	165.50			19	15	34	.57		.43			
489.0	491.5	75064	2.5	.0	2D0	3.52	.18	3.75	6.19	81.20			11	12	23	2.71		.22			
491.5	494.0	75065	2.5	.0	2D0	3.05	.09	1.29	3.26	28.00			5	6	12	2.58		.08			
494.0	496.5	75066	2.5	.0	2C0	3.03	.11	.33	.98	13.30			6	6	13	3.30		.05			
496.5	499.0	75067	2.5	.0	****	3.09	.08	.50	1.20	8.40			6	6	13	3.80		.02			
499.0	501.5	75068	2.5	.0	2C0	3.02	.11	1.31	2.83	25.50			6	5	11	2.56		.04			
501.5	504.0	75069	2.5	.0	2D0	2.97	.08	1.27	4.09	24.90			5	4	10	.30		.05			
504.0	506.5	75070	2.5	.0	2C0	2.98	.10	.69	1.75	13.40			7	4	11	2.58		.02			
506.5	509.0	75071	2.5	.0	2C0	3.21	.14	2.45	4.74	42.00			13	3	16	2.35		.05			
509.0	511.0	75072	2.0	.0	2H49	4.32	.25	5.25	9.85	61.00			29	7	36	2.28		.08			
511.0	513.5	75073	2.5	.0	2H4	4.54	.15	3.97	6.12	51.00			13	21	34	1.00		.08			
513.5	516.0	75074	2.5	.0	2H9	4.29	.22	2.31	2.59	28.60			16	21	38	.07		.12			
516.0	519.0	75075	3.0	.0	2H9	4.38	.39	3.24	4.06	115.10			18	18	37	.26		.12			
519.0	522.0	75076	3.0	.0	2E41	3.90	.16	8.73	13.70	113.80			18	10	28	.06		.37			
522.0	525.0	75077	3.0	.0	2E41	4.34	.22	8.23	11.10	138.70			17	13	30	.07		.34			
525.0	527.5	75078	2.5	.0	2H9	4.54	.32	3.88	4.31	70.30			36	4	41	3.25		.29			
527.5	531.0	75079	3.5	.0	2E46	4.07	.19	4.56	3.88	79.90			16	20	37	5.32		.28			
545.0	549.5	75081	4.5	.0	2E39	4.00	.30	1.82	.50	28.90			18	23	42	4.65		.19			
549.5	552.0	75082	2.5	.0	2H49	4.34	.44	4.81	6.67	72.50			29	13	43	.05		.26			
552.0	554.0	75083	2.0	.0	2G4	4.37	.13	5.99	8.63	97.70			6	17	24	22.49		.21			
554.0	557.0	75084	3.0	.0	2G4	4.49	.05	6.17	8.73	98.00			2	14	17	40.62		.09			
557.0	560.0	75085	3.0	.0	2G4	4.42	.15	5.65	8.56	85.80			5	15	21	30.82		.16			
560.0	562.5	75086	2.5	.0	2E41	4.66	.04	2.72	3.03	29.20			3	35	39	.18		.10			
562.5	565.0	75087	2.5	.0	2E1	4.63	.05	.93	1.24	9.60			1	39	41	.07		.04			
565.0	567.5	75088	2.5	.0	2E1	4.68	.21	1.90	1.24	17.10			1	39	40	.13		.04			
567.5	570.0	75089	2.5	.0	2E1	4.25	.04	.55	.47	11.50				35	36	.06		.01			
570.0	572.5	75090	2.5	.0	2E1	4.72	.08	.05	.09	9.00				44	45	.05		.01			
572.5	575.0	75091	2.5	.0	2E41	4.70	.04	2.43	4.16	19.30				37	38	7.02		.01			
575.0	577.5	75092	2.5	.0	2E41	4.78	.04	4.05	6.56	32.70				34	35	5.91		.01			
577.5	580.0	75093	2.5	.0	2E41	4.56	.14	2.77	2.31	28.00			1	38	39	.07		.04			
580.0	582.5	75094	2.5	.0	2E41	4.85	.28	3.39	2.59	40.70			1	40	41	.05		.06			
582.5	585.0	75095	2.5	.0	2E1	4.34	.04	.47	.51	11.80			1	36	38	.08		.07			
585.0	587.5	75096	2.5	.0	2E1	3.94	.07	.31	.22	11.50			3	28	32	.04		.05			
587.5	590.0	75097	2.5	.0	2E49	4.20	.34	1.68	2.91	26.10			11	23	35	2.56		.10			
590.0	593.0	75098	3.0	.0	2D9	3.14	.24	2.45	4.73	34.20			7	5	13	.46		.07			
593.0	596.5	75099	3.5	.0	2D9	3.04	.81	1.57	4.21	26.70			4	6	11	.58		.05			
596.5	599.5	75100	3.0	.0	2E4	4.64	.10	3.46	6.13	37.30			5	35	40	.06		.06			
599.5	602.0	75101	2.5	.0	2E4	4.57	.13	5.05	6.71	24.90			4	31	36	.05		.24			
602.0	604.5	75102	2.5	.0	2E4	4.70	.40	6.29	6.46	34.50			2	35	38	.06		.12			
604.5	607.0	75103	2.5	.0	2E49	4.85	.25	5.16	6.12	30.80			1	37	39	.05		.07			
607.0	609.5	75104	2.5	.0	2E4	4.80	.11	3.55	6.40	19.60			1	37	39	.04		.04			

DDH: 80-07 UTM-N: 8674.8 UTM-E: 14718.2 UTM-ELEV: 4031.2 TOTAL DEPTH: 699.0 SECTION: 122+020
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

-----DEPTHS-----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
609.5	612.0	75105	2.5	.0	2E4	4.78	.07	3.53	6.32	23.00			4	37	42	.05		.02			
612.0	614.5	75106	2.5	.0	2E49	4.85	.23	1.67	1.96	16.80			1	43	44	.03		.01			
614.5	617.0	75107	2.5	.0	2E4	4.91	.06	2.93	4.70	14.60			1	41	42	.03		.02			
617.0	619.5	75108	2.5	.0	2E4	4.87	.12	2.87	4.80	22.40			1	40	42	.04		.02			
619.5	623.0	75109	3.5	.0	2H9	4.31	.47	3.22	6.61	51.90			41	4	45	.07		.07			
623.0	626.0	75110	3.0	.0	2H9	4.24	.58	2.99	6.31	49.80			41	7	49	.05		.07			
626.0	628.5	75111	2.5	.0	2D49	3.29	.25	3.60	8.05	43.50			8	5	14	.32		.07			
628.5	631.0	75112	2.5	.0	2D49	3.37	.18	9.70	3.55	150.80			6	7	14	.33		.05			
631.0	633.5	75113	2.5	.0	2F9	4.04	.26	4.92	4.45	354.60			6	22	28	.14		.07			
633.5	636.0	75114	2.5	.0	2D0	3.21	.15	1.68	3.67	88.00			3	9	13	.14		.05			
636.0	638.0	75115	2.0	.0	2D0	2.95	.12	1.30	4.33	37.00			4	3	7	.25		.04			
638.0	640.0	75116	2.0	.0	2H0	4.45	.63	3.29	6.15	19.60			35	6	42	.39		.04			
640.0	642.5	75117	2.5	.0	2E4	4.55	.14	4.85	8.68	24.60			4	28	32	.06		.03			
642.5	645.0	75118	2.5	.0	2E4	5.06	.03	4.14	5.61	11.80			2	30	32	.03		.03			
645.0	647.5	75119	2.5	.0	2E4	4.95	.04	4.81	5.22	49.10			3	33	36	.04		.05			
647.5	650.0	75120	2.5	.0	2E4	4.87	.02	6.17	7.29	19.90			3	34	37	.05		.05			
650.0	652.5	75121	2.5	.0	2E4	5.02	.03	3.56	5.07	11.20			1	33	35	.05		.03			
652.5	655.0	75122	2.5	.0	2E4	4.89	.01	7.42	10.18	131.90			2	32	34	.04		.03			
655.0	657.5	75123	2.5	.0	2E4	5.32	.01	6.11	7.01	18.40			1	35	37	.04		.02			
657.5	660.0	75124	2.5	.0	2E4	5.12	.02	5.28	11.30	19.00			2	32	34	.04		.03			
660.0	662.0	75125	2.0	.0	2E41	4.04	.03	3.35	7.44	12.40			1	26	27	.07		.04			
662.0	664.5	75126	2.5	.0	2F41	4.16	.02	4.22	9.12	14.30			1	26	28	.08		.04			
664.5	667.0	75127	2.5	.0	2F41	4.34	.92	6.08	14.80	23.60			2	25	28	.06		.03			
667.0	670.0	75128	3.0	.0	2E41	3.38	.03	1.12	4.68	10.60			1	16	18	.09		.03			
670.0	672.5	75129	2.5	.0	2E41	3.54	.04	2.76	8.43	17.70			2	17	20	.05		.05			
672.5	675.0	75130	2.5	.0	2A41	3.37	.12	4.57	11.30	60.70			3	8	11	.08		.04			
675.0	678.0	75131	3.0	.0	2A41	3.02	.21	3.21	6.49	69.00			3	2	5	.13		.04			
678.0	680.5	75132	2.5	.0	2A41	3.56	.36	1.03	6.62	19.60			8	13	21	.09		.07			
680.5	683.0	75133	2.5	.0	2D39	3.28	.36	1.43	6.69	22.10			6	9	16	.20		.04			
683.0	685.5	75134	2.5	.0	2D39	3.33	.37	.95	6.00	23.00			7	13	20	.18		.04			
685.5	688.0	75135	2.5	.0	2D39	3.43	.50	1.40	3.64	21.50			8	15	24	.15		.08			
688.0	690.5	75136	2.5	.0	2D39	3.22	.29	1.86	7.38	24.30			5	12	17	.16		.04			
690.5	693.0	75137	2.5	.0	2D0	2.98	.18	2.18	5.49	28.60			4	3	7	.30		.01			
693.0	695.5	75138	2.5	.0	2D0	3.00	.16	1.89	7.02	29.90			3	4	8	.36		.06			
695.5	699.0	75139	3.5	.0	2D43	3.35	.28	7.91	5.31	133.10			10	4	15	.17		.02			

DDH: 80-08 UTM-N: 9060.8 UTM-E: 14675.2 UTM-ELEV: 3954.5 TOTAL DEPTH: 601.0 SECTION: 120+000
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

-----DEPTHS-----		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
409.0	412.0	75143	3.0	.0	2L14	3.32	.05	4.32	7.78	128.80			4	3	8	15.65		.15			
412.0	414.5	75144	2.5	.0	2D4	3.98	.13	5.55	7.81	111.00			11	14	25	6.89		.26			
414.5	417.0	75145	2.5	.0	2G1	3.07	.10	1.85	2.21	31.70			7	6	14	13.98		.13			
417.0	419.5	75146	2.5	.0	2G4	4.07	.17	4.29	5.84	89.90			14	8	22	16.15		.20			
419.5	422.0	75147	2.5	.0	2D46	3.61	.19	5.30	7.06	128.10			12	12	24	3.05		.33			
422.0	425.0	75148	3.0	.0	2L14	3.22	.19	1.85	2.09	38.60			11	9	20	4.47		.19			
425.0	428.0	75149	3.0	.0	2L14	2.82	.06	.27	.34	6.80			15	5	20	.92		.16			
428.0	430.5	75150	2.5	.0	2D6I	3.77	.16	5.71	3.12	128.10			4	12	16	12.98		.14			
430.5	433.0	75151	2.5	.0	2C6I	3.03	.22	1.64	.64	37.00			4	5	10	11.48		.13			
433.0	435.5	75152	2.5	.0	2C6	2.97	.10	.42	.33	12.40			3	3	7	8.89		.12			
435.5	437.5	75153	2.0	.0	2C69	3.24	.30	2.06	1.70	38.30			6	12	18	5.47		.32			
437.5	440.0	75154	2.5	.0	2E41	4.57	.29	4.32	3.91	68.70			6	22	28	5.55		.23			
440.0	442.5	75155	2.5	.0	2E09	4.68	.24	4.17	4.11	65.60			5	26	32	7.47		.25			
442.5	445.0	75156	2.5	.0	2E49	5.56	.20	1.91	2.20	29.20			2	37	39	.22		.09			
445.0	447.5	75157	2.5	.0	2E09	4.67	.31	1.95	1.26	25.20			2	33	36	.57		.09			
447.5	450.0	75158	2.5	.0	2E0	4.52	.16	1.34	1.41	18.70			1	36	37	.34		.02			
450.0	452.5	75159	2.5	.0	2E0	4.54	.14	.74	.69	15.20			1	37	39	.10		.04			
452.5	455.0	75160	2.5	.0	2E4	4.15	.06	1.85	2.89	17.70			1	30	32	.45		.03			
455.0	457.5	75161	2.5	.0	2E4	4.71	.16	3.85	5.92	38.30			2	34	36	.10		.07			
457.5	460.0	75162	2.5	.0	2E0	5.89	.12	1.30	.63	19.00				39	40	.45					
460.0	462.5	75163	2.5	.0	2E0	4.03	.12	1.51	.75	21.20				39	40	.57		.01			
462.5	465.0	75164	2.5	.0	2E0	4.47	.09	2.24	1.44	32.00			1	35	36	.10		.01			
465.0	467.5	75165	2.5	.0	2E0	4.22	.13	1.08	.69	17.70			1	34	35	.34		.03			
467.5	470.0	75166	2.5	.0	2E0	4.77	.12	1.82	1.83	27.70			1	39	40	.34		.02			
470.0	472.5	75167	2.5	.0	2E0	4.32	.14	1.64	1.27	26.40			2	32	35	.45		.03			
472.5	475.0	75168	2.5	.0	2E09	3.93	.29	1.84	1.13	33.60			2	32	34	.57		.08			
475.0	478.0	75169	3.0	.0	2E49	4.75	.36	2.50	1.69	48.50			3	35	38	.22		.16			
478.0	481.0	75170	3.0	.0	2E09	3.29	.34	1.68	.66	36.70			3	34	37	.22		.10			
481.0	483.5	75171	2.5	.0	2E6	4.98	.10	.99	1.22	30.80			1	33	35	3.13		.05			
483.5	486.0	75172	2.5	.0	2G4	4.42	.06	2.94	7.60	42.90			1	9	11	20.91		.05			
486.0	488.5	75173	2.5	.0	2E06	4.51	.36	1.52	2.46	26.10			6	30	37	4.80		.29			
488.5	491.0	75174	2.5	.0	2E89	5.64	.46	1.37	1.68	29.20			10	27	38	.22		.30			
491.0	493.5	75175	2.5	.0	2E48	4.50	.40	4.13	4.85	56.90			8	28	37	.10		.34			
493.5	496.0	75176	2.5	.0	2E48	4.64	.19	9.15	3.30	131.90			3	29	32	.10		.12			
496.0	498.5	75177	2.5	.0	2E48	4.45	.33	2.42	4.11	74.30			8	28	37	.34		.39			
498.5	501.5	75178	3.0	.0	2E48	4.35	.32	1.61	3.34	23.00			10	26	37	.22		.46			
501.5	504.5	75179	3.0	.0	2E48	4.61	.40	1.55	2.91	20.50			9	29	39	.69		.45			
504.5	507.0	75180	2.5	.0	2E48	4.71	.25	1.98	3.26	21.20			5	32	37	.22		.38			
507.0	509.5	75181	2.5	.0	2E19	4.80	.44	.82	.43	13.40			1	40	41	.22		.15			
509.5	512.0	75182	2.5	.0	2E1	4.68	.12	1.43	1.79	15.60			2	34	37	.10		.02			
512.0	514.0	75183	2.0	.0	2E41	4.44	.27	2.84	3.88	23.90			6	28	35	.34		.07			
514.0	516.0	75184	2.0	.0	2E48	4.68	.26	1.65	2.51	15.90			4	34	38	.22		.24			
516.0	518.0	75185	2.0	.0	2E48	4.81	.17	2.47	2.98	22.40			4	33	38	.10		.15			
518.0	520.0	75186	2.0	.0	2E89	4.73	.31	.87	2.10	15.60			8	31	39	.22		.30			
520.0	522.5	75187	2.5	.0	2E48	4.37	.52	2.75	2.80	40.70			8	26	34	.34		.35			
522.5	525.0	75188	2.5	.0	2E89	4.61	.23	1.12	1.56	15.90			9	31	41	.22		.45			
525.0	527.5	75189	2.5	.0	2E1	4.92	.19	.24	.32	19.60			5	35	41	.10		.18			
527.5	530.0	75190	2.5	.0	2E19	4.89	.24	.24	.21	12.40			3	36	40	.57		.11			
530.0	532.5	75191	2.5	.0	2E41	4.52	.15	3.20	4.68	22.70			6	31	37	.57		.17			
532.5	535.0	75192	2.5	.0	2E1	4.32	.15	1.60	1.64	14.60			7	29	37	.34		.22			
535.0	537.5	75193	2.5	.0	2E1	4.22	.15	1.32	1.74	14.00			4	28	33	.34		.11			

DDH: 80-08 UTM-N: 9060.8 UTM-E: 14675.2 UTM-ELEV: 3954.5 TOTAL DEPTH: 601.0 SECTION: 120+000
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

-----DEPTHS-----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
537.5	540.0	75194	2.5	.0	2F0	4.50	.16	2.70	5.49	15.60			3	25	29	.22		.09			
540.0	542.5	75195	2.5	.0	2F4	4.36	.17	2.94	7.24	14.30			5	25	31	.22		.16			
542.5	545.0	75196	2.5	.0	2F41	4.34	.27	7.39	12.40	18.70			4	22	26	.22		.16			
545.0	547.5	75197	2.5	.0	2E19	4.19	.37	1.97	4.43	10.60			6	26	32	.34		.19			
547.5	550.0	75198	2.5	.0	2E1	4.28	.20	.99	2.90	10.90			3	30	33	.22		.09			
550.0	552.5	75199	2.5	.0	2E41	4.40	.16	1.83	3.87	15.60			3	28	32	.10		.09			
552.5	555.0	75200	2.5	.0	2E41	4.50	.17	2.63	4.17	14.60			2	31	34	.57		.07			
555.0	557.5	75201	2.5	.0	2E41	4.75	.27	2.51	3.95	16.50			1	35	36	.45		.02			
557.5	560.0	75202	2.5	.0	2F0	4.73	.19	2.80	5.17	19.00			1	35	36	.10		.02			
560.0	562.5	75203	2.5	.0	2F0	4.62	.27	2.78	4.46	16.20			1	35	36	.10		.01			
562.5	565.0	75204	2.5	.0	2F4	4.86	.07	3.51	6.69	21.20			1	33	35	.10		.01			
565.0	567.5	75205	2.5	.0	2E41	4.74	.06	6.12	10.20	26.40			2	29	31	.10		.02			
567.5	570.0	75206	2.5	.0	2E41	4.25	.05	3.75	8.24	14.90			2	26	28	.10		.02			
570.0	572.5	75207	2.5	.0	2E48	4.35	.44	2.05	4.46	13.40			3	35	39	.34		.09			
572.5	575.0	75208	2.5	.0	2E48	4.41	.40	1.20	3.99	12.10			5	31	36	.34		.17			
575.0	577.0	75209	2.0	.0	2F9	4.94	.39	1.18	3.91	12.40			5	30	36	.22		.17			
577.0	579.0	75210	2.0	.0	2D30	4.86	.12	2.14	4.13	11.80			1	38	39	.10					
579.0	581.5	75211	2.5	.0	2D43	3.50	.08	3.96	7.56	15.90			1	33	34	.10		.02			
581.5	584.0	75212	2.5	.0	2D43	3.93	.16	4.22	7.59	27.70			15	13	28	.10		.02			
584.0	586.5	75213	2.5	.0	2D9	3.66	.33	1.70	2.39	27.10			9	15	24	.34		.02			
586.5	589.0	75214	2.5	.0	2C0	3.13	.07	.96	2.72	12.80			3	9	13	.81		.04			
589.0	591.5	75215	2.5	.0	2D4	2.98	.10	3.72	5.03	42.90			3	3	7	.81		.03			
591.5	594.0	75216	2.5	.0	2D4	3.28	.06	7.44	10.10	131.30			4	8	13	.45		.08			
594.0	596.5	75217	2.5	.0	2D0	2.89	.06	1.95	5.01	25.50			2	1	4	.57		.03			
596.5	599.0	75218	2.5	.0	2A4	2.92	.04	1.28	4.60	21.50			1	1	3	1.27		.03			
599.0	600.0	75219	1.0	.0	2A4	2.84	.05	1.25	3.16	24.90			1	2	4	1.04		.02			
600.0	601.0	75220	1.0	.0	2A4	2.84	.05	1.25	3.16	24.90			1	2	4	1.04		.02			

DDH: 81-01 UTM-N: 7594.5 UTM-E: 15399.6 UTM-ELEV: 4002.9 TOTAL DEPTH: 320.0 SECTION: 131
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
197.0	208.0	75223	11.0	.0	2D0	3.01	.11	4.65	3.90	129.90				3	4	7	.26				.07
218.0	220.5	75225	2.5	.0	2A4	2.77	.04	1.96	2.47	47.90		.21	1	1	3	.31				.01	
220.5	223.0	75226	2.5	.0	2A0	2.76	.06	.84	2.07	28.60		.27	2	2	4	.34				.01	
223.0	225.5	75227	2.5	.0	2A4	2.95	.11	1.94	4.03	58.20		.41	3	5	9	.23				.04	
225.5	228.0	75228	2.5	.0	2A4	3.07	.11	1.86	4.43	54.40		.14	4	7	11	.32				.03	
228.0	232.2	75229	4.2	.0	2A4	2.92	.16	1.81	4.81	54.40		1.03	3	6	9	.35				.02	
232.2	233.4	75230	1.2	.0	2D0	2.94	.09	2.37	4.34	59.40		1.10	4	3	8	.27				.04	
233.4	238.4	75231	5.0	.0	2A4	2.86	.07	2.00	4.71	64.10		.27	3	3	7	.32				.02	
238.4	243.0	75232	4.6	.0	2A4	2.88	.06	1.82	4.60	56.60		1.17	3	3	6	.34				.02	
243.0	248.0	75233	5.0	.0	2A4	2.67	.04	1.23	2.78	25.20		.27	1	1	3	.37					
248.0	251.6	75234	3.6	.0	2A4	2.58	.05	1.86	2.67	31.40		.41	1	1	3	.36					
251.6	256.6	75235	5.0	.0	2A0	2.82	.10	.46	.65	16.80		.27	3	4	8	.20				.01	
256.6	261.5	75236	4.9	.0	2A4	2.80	.06	2.10	2.33	36.10		.21	2	2	4	.29				.03	
261.5	266.0	75237	4.5	.0	2B0	2.85	.20	.16	.26	6.50		1.17	4	6	11	.20				.06	

DDH: 81-02 UTM-N: 7711.3 UTM-E: 15102.5 UTM-ELEV: 3994.5 TOTAL DEPTH: 400.0 SECTION: 129
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
276.0	277.2	75242	1.2	.0	2AF	3.46	.13	1.29	2.99	20.50		1.03	6	13	20	.10		.12			
277.2	279.0	75243	1.8	.0	2F4	4.36	.08	4.83	6.22	63.40		.34	8	15	24	.07		.23			
279.0	282.0	75244	3.0	.0	2B0	2.92	.13	.52	2.19	12.40		.07	4	4	9	.70		.05			
282.0	284.3	75245	2.3	.0	2E4	4.23	.33	2.79	3.55	44.80		.07	15	15	30	.05		.22			
284.3	287.3	75246	3.0	.0	2F0	4.52	.23	2.38	2.73	23.00		.07	7	21	29	.06		.10			
287.3	290.1	75247	2.8	.0	2F0	4.41	.23	3.33	4.88	36.10		.07	8	20	28	.03		.11			
290.1	293.0	75248	2.9	.0	2A4	3.13	.24	1.98	3.68	39.80		.41	9	6	15	.31		.11			
293.0	296.0	75249	3.0	.0	2C0	2.81	.07	.82	1.89	21.20		.21	2	2	4	.51		.01			
296.0	299.0	75250	3.0	.0	2C0	2.82	.10	.96	2.36	27.40		.07	3	2	6	.52		.01			
299.0	302.0	75251	3.0	.0	2C0	2.79	.09	.96	2.82	30.20		.96	3	2	6	.52		.03			
302.0	306.0	75252	4.0	.0	2C0	2.87	.15	.74	2.67	32.70		.21	3	5	8	.48		.04			
306.0	308.0	75253	2.0	.0	2C0	2.87	.08	.73	1.61	28.90		.07	4	3	8	.53		.05			
308.0	312.0	75254	4.0	.0	2A0	2.88	.08	.96	1.92	27.40		.75	3	3	6	.42		.02			
312.0	316.0	75255	4.0	.0	2A0	2.73	.05	.84	1.87	20.50		.34	2	1	4	.40		.02			
316.0	320.0	75256	4.0	.0	2A0	2.67	.04	.46	1.35	13.10		.17	2	1	4	.37		.02			
320.0	324.5	75257	4.5	.0	2A0	2.79	.10	1.00	1.81	31.70		.07	3	3	7	.32		.05			

DDH: 81-03 UTM-N: 7503.2 UTM-E: 15105.3 UTM-ELEV: 4011.6 TOTAL DEPTH: 384.0 SECTION: 130
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
292.6	295.3	75261	2.7	.0	2D4	3.45	.07	4.69	8.50	43.90		.34	4	10	15	.17		.11			
295.3	299.3	75262	4.0	.0	2D0	2.93	.10	1.34	3.01	31.40		.07	3	4	8	.56		.08			
299.3	303.0	75263	3.7	.0	2C0	2.92	.08	.79	1.71	22.70		.14	3	5	8	.67		.05			
303.0	307.0	75264	4.0	.0	2C0	2.80	.04	.72	1.56	22.10		.27	2	1	4	.79		.04			
310.0	311.0	75266	1.0	.0	2F0	4.10	.20	3.38	4.23	53.50		.07	8	16	25	.34		.13			
311.0	314.0	75267	3.0	.0	1D49	2.86	.07	.20	1.03	10.00		.07	3	3	7	.90		.06			
337.0	338.0	75271	1.0	.0	1D49	3.49	.20	6.42	1.51	125.60		.07	8	10	18	.28		.05			

DDH: 81-04 UTM-N: 7297.5 UTM-E: 15299.4 UTM-ELEV: 4018.7 TOTAL DEPTH: 305.0 SECTION: 132
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
184.1	185.4	75275	1.3	.0	2F4	4.10	.11	7.89	8.87	150.80		.75	7	16	24	.31		.20			
190.8	192.0	75277	1.2	.0	2D4	3.21	.29	6.07	7.96	126.90		.55	4	7	11	.24		.13			
192.0	194.7	75278	2.7	.0	2F4	4.25	.27	6.86	7.43	130.90		.27	10	17	28	.38		.37			
194.7	195.6	75279	.9	.0	2BC	3.06	.35	2.74	2.52	51.60		.62	5	7	13	2.05		.14			
197.3	200.3	75281	3.0	.0	2DG	3.19	.26	2.81	2.56	50.10		.07	5	6	11	8.58		.16			
200.3	201.6	75282	1.3	.0	2BC	2.84	.04	.57	.97	10.60		.07	2	2	4	8.25		.06			
201.6	204.0	75283	2.4	.0	2L19	2.97	.07	3.48	2.59	98.30		2.47	2	5	7	3.87		.10			
204.0	205.4	75284	1.4	.0	2L19	3.37	.09	7.64	7.34	130.00		.07	6	8	15	.40		.18			
205.4	208.0	75285	2.6	.0	2C0	2.93	.07	.71	1.79	16.20		.07	4	6	10	.92		.03			
208.0	210.5	75286	2.5	.0	2C0	2.73	.03	.82	1.94	17.10		.07	1	2	3	.80		.01			
210.5	214.5	75287	4.0	.0	2C0	2.75	.03	.86	1.48	11.80		.07	1	1	3	2.25		.03			
223.0	226.8	75289	3.8	.0	2EF	4.20	.42	3.72	4.33	56.30		.07	15	18	33	.24		.11			
226.8	228.8	75290	2.0	.0	2F4	4.13	.33	5.74	9.22	81.80		.07	10	16	26	.45		.12			
230.0	235.0	75292	5.0	.0	2A0	2.73	.09	1.79	1.56	32.30		.41	3	3	7	.98		.02			
235.0	241.5	75293	6.5	.0	2A0	2.74	.05	.59	.88	13.70		.34	3	2	6	.56		.05			
241.5	245.2	75294	3.7	.0	2C0	2.81	.06	1.00	1.61	19.90		.48	2	3	6	.90		.02			
245.2	248.2	75295	3.0	.0	2A0	2.98	.11	.95	1.63	24.90		.55	9	4	14	.67		.06			
248.2	251.8	75296	3.6	.0	2A0	3.01	.09	.79	1.52	12.40		.48	5	6	12	.70		.01			
251.8	255.1	75297	3.3	.0	2A0	2.73	.04	.95	1.47	26.40		.07	2	1	3	1.05					
255.1	258.6	75298	3.5	.0	2C0	2.88	.14	1.43	2.11	64.40		.75	3	3	7	.90		.04			
258.6	262.4	75299	3.8	.0	2C0	2.93	.11	2.48	2.82	93.90		.07	4	4	8	.23		.05			
262.4	264.0	75300	1.6	.0	2A0	2.76	.09	.91	1.76	45.10		.27	4	2	6	.88		.04			
264.0	270.2	75301	6.2	.0	2A0	2.78	.13	.56	1.47	24.30		.48	3	3	6	.29		.03			

DDH: 81-05 UTM-N: 7091.8 UTM-E: 15304.1 UTM-ELEV: 4005.8 TOTAL DEPTH: 252.0 SECTION: 133
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
134.9	138.2	75306	3.3	.0	2D4	3.51	.12	5.76	11.80	64.10		.41	3	11	14	.21		.04			
138.2	140.5	75307	2.3	.0	2F4	4.30	.11	6.83	8.77	265.30		.34	6	19	25	.17		.27			
140.5	144.5	75308	4.0	.0	2D0	2.85	.07	2.29	3.93	49.80		.07	3	2	5	.67		.10			
144.5	146.8	75309	2.3	.0	2B0	2.63	.03	.63	2.28	18.40		.21	1		1	1.12		.01			
146.8	150.0	75310	3.2	.0	2A0	2.69	.03	1.04	2.48	20.80		.07	1		1	1.04		.01			
150.0	153.0	75311	3.0	.0	2A0	2.71	.03	1.52	2.12	45.40		.21	1	1	2	1.08		.01			
153.0	155.5	75312	2.5	.0	2D4	3.24	.06	11.10	6.81	348.30		.34	4	5	9	.17		.07			
155.5	158.0	75313	2.5	.0	2D4	3.02	.06	4.71	6.70	106.90		7.68	5	4	9	.06		.14			
158.0	161.0	75314	3.0	.0	2D0	2.81	.06	1.83	2.56	30.50		.07	3	4	7	.19		.05			
161.0	163.5	75315	2.5	.0	2B0	2.75	.04	.76	1.50	14.30		.48	2	2	4	.46		.04			
163.5	166.0	75316	2.5	.0	2B0	2.82	.05	.99	2.52	19.60		.41	3	3	6	.60		.05			
166.0	168.0	75317	2.0	.0	2C0	3.00	.09	.41	1.16	8.40		.48	4	7	12	.40		.06			
168.0	170.0	75318	2.0	.0	2B0	2.69	.04	.71	1.90	12.40		.07	2	1	4	.82		.02			
170.0	172.0	75319	2.0	.0	2B0	2.73	.06	.41	.30	14.00		.34	3	2	5	.43		.03			
172.0	175.3	75320	3.3	.0	2A0	2.76	.06	.55	.82	13.10		.07	2	2	5	.52		.04			

DDH: 81-06 UTM-N: 7296.6 UTM-E: 15508.9 UTM-ELEV: 4010.5 TOTAL DEPTH: 273.0 SECTION: 133
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----		-----ASSAYS-----																			
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
100.2	107.3	75325	7.1	.0	2C0	2.96	.11	.37	.45	17.40		.07	5	6	11	.20		.03			
107.3	113.0	75326	5.7	.0	2D0	3.52	.16	3.35	4.63	66.60		.07	7	12	20	.25		.09			
113.0	119.0	75327	6.0	.0	2EA	3.28	.06	3.37	3.82	60.30		.07	10	7	18	2.43		.19			
119.0	127.3	75328	8.3	.0	2D0	3.01	.08	2.87	4.47	45.40		.07	3	7	11	.42		.14			
127.3	130.0	75329	2.7	.0	2E4	4.44	.08	2.73	4.50	24.90		.07	4	23	28	.18		.08			
130.0	132.8	75330	2.8	.0	2F0	4.22	.15	2.37	4.07	47.00		.07	4	22	26	.27		.05			
132.8	134.1	75331	1.3	.0	2E4	4.31	.28	3.48	6.99	76.80		.07	11	18	30	.10		.08			
134.1	138.0	75332	3.9	.0	2EF	4.49	.14	4.82	6.70	63.40		.07	5	22	27	.27		.08			
138.0	140.4	75333	2.4	.0	2EF	4.21	.15	5.03	7.05	71.50		.07	8	21	30	.20		.15			
140.4	144.1	75334	3.7	.0	2A0	2.92	.06	1.47	2.33	43.20		.41	2	5	8	.84		.02			
144.1	147.4	75335	3.3	.0	2A0	2.70	.03	.50	1.07	19.00		.07	2	1	4	.69					
147.4	151.5	75336	4.1	.0	2A0	2.69	.02	.85	2.31	19.00		.48	1	1	2	.87		.01			
151.5	154.0	75337	2.5	.0	2A0	2.60	.04	1.02	1.79	19.30		.34	1	1	3	.65					
154.0	158.7	75338	4.7	.0	2A0	2.69	.06	.69	1.25	13.70		.34	2	2	4	.36					

DDH: 81-07 UTM-N: 7402.5 UTM-E: 15604.1 UTM-ELEV: 4009.8 TOTAL DEPTH: 190.0 SECTION: 133
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
6 53.0	61.0	75342	8.0	.0	2E14	3.76	.14	3.01	5.44	56.30		.07	5	16	21	.49		.10			
5 61.0	67.5	75343	6.5	.0	2A14	2.98	.06	1.42	4.21	24.90		1.30	4	6	10	.43		.04			
0 67.5	76.0	75344	8.5	.0	2A1	3.00	.10	1.07	2.78	25.80		1.23	5	6	11	1.11		.04			
6 76.0	78.0	75345	2.0	.0	2E14	3.44	.13	1.85	5.98	31.70		.07	8	12	20	.39		.06			
	78.0	83.0	75346	5.0	.0	2C2	3.38	.13	1.35	1.36	22.70		.34	6	13	20	.55		.04		
	83.0	87.7	75347	4.7	.0	2C2	3.13	.08	1.43	1.96	25.50		1.30	5	9	15	.47		.03		
0 87.7	96.0	75348	8.3	.0	2C0	3.00	.08	.48	1.24	13.70		.62	7	7	14	.62		.08			
	96.0	103.0	75349	7.0	.0	2A0	2.80	.06	.64	1.44	16.80		.41	7	3	10	.56		.08		
	103.0	106.0	75350	3.0	.0	2A/1D	2.60	.04	.86	1.92	18.70		.55	2	1	3	.34		.02		

DDH: 81-08 UTM-N: 7703.7 UTM-E: 15651.8 UTM-ELEV: 4016.4 TOTAL DEPTH: 288.0 SECTION: 132
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
6	174.0	176.0	75354	2.0	.0	2D4	3.45	.14	7.73	15.40	8.40		.82	6	6	13	.02		.15		
	176.0	178.2	75355	2.2	.0	2D4	3.46	.16	7.22	16.70	67.50		.34	6	7	13	.02		.13		
6	178.2	180.5	75356	2.3	.0	2C3	3.52	.14	.62	1.47	14.00		.34	7	14	22	.11		.06		
	180.5	182.9	75357	2.4	.0	2C3	3.28	.04	.75	.59	13.40		.34	2	14	16	.24		.03		
6	182.9	186.5	75358	3.6	.0	2D4	3.48	.10	7.34	9.85	113.50		.72	7	7	14	3.71		.17		
	186.5	191.0	75359	4.5	.0	1D9	2.90	.05	1.38	1.52	29.90		.34	5	4	9	4.07		.14		
6	191.0	196.0	75360	5.0	.0	1D9	2.94	.04	1.36	1.60	28.90		.62	6	4	11	3.29		.15		
	196.0	198.3	75361	2.3	.0	1D4	2.90	.05	.70	.76	19.00		.62	7	6	13	3.39		.11		
	198.3	199.8	75362	1.5	.0	2C3	3.57	.19	1.00	1.11	28.00		.27	11	12	23	5.49		.09		
	199.8	201.9	75363	2.1	.0	1D4	2.95	.05	.70	.58	14.90		.34	5	4	9	12.40		.12		
6	201.9	205.0	75364	3.1	.0	2D4	3.20	.08	3.46	7.48	68.10		.96	6	8	15	2.73		.23		
	205.0	209.0	75365	4.0	.0	2D0	3.81	.06	1.63	3.83	33.90		.48	3	4	7	.18		.06		
6	209.0	213.0	75366	4.0	.0	2D0	2.85	.04	1.63	3.93	30.20		1.03	3	3	6	.40		.04		
	213.0	217.0	75367	4.0	.0	2D0	2.90	.05	2.47	2.86	45.40		.34	3	4	7	.13		.03		
4	217.0	221.0	75368	4.0	.0	2D0	2.91	.05	1.54	3.37	26.10		.75	3	4	8	.36		.04		
	221.0	223.4	75369	2.4	.0	2F4	4.33	.12	6.06	9.34	73.70		1.65	7	19	27	.06		.08		
6	223.4	226.8	75370	3.4	.0	2F4	4.62	.04	7.96	12.10	75.90		.55	1	22	24	.04		.02		
	226.8	230.8	75371	4.0	.0	2E0	4.64	.39	1.45	.84	25.80		2.33	5	27	32	.04		.18		
	230.8	233.4	75372	2.6	.0	2E0	4.66	.43	.28	.36	14.90		.07	5	29	34	.03		.14		
6	233.4	235.4	75373	2.0	.0	2E1	4.39	.30	.85	.95	17.70		.07	4	27	31	.03		.15		
	235.4	239.0	75374	3.6	.0	2E1	4.21	.16	1.25	1.93	16.80		.07	5	21	26	.03		.24		
6	239.0	244.1	75375	5.1	.0	2E14	4.44	.21	4.89	7.77	51.00		.07	7	19	26	.03		.21		
	244.1	247.0	75376	2.9	.0	2E0	4.08	.23	1.06	2.25	19.30		.34	10	18	28	.04		.29		
6	247.0	248.3	75377	1.3	.0	2E1	3.96	.50	1.71	2.89	27.10		.14	18	12	30	.06		.09		
	248.3	250.0	75378	1.7	.0	2H84	4.39	.12	4.10	7.26	34.20		.07	6	19	25	.04		.18		
	250.0	255.5	75379	5.5	.0	2F0	3.15	.11	1.77	6.90	25.20		.27	5	6	12	.29		.10		
6	255.5	260.5	75380	5.0	.0	2A4	2.91	.03	2.40	6.69	21.20		.07	2	3	5	.31		.03		
	260.5	266.7	75381	6.2	.0	2A4	2.92	.04	2.42	4.79	29.90		.69	2	3	6	.24		.03		

DDH: 81-10 UTM-N: 7922.9 UTM-E: 15325.7 UTM-ELEV: 4016.1 TOTAL DEPTH: 538.0 SECTION: 129
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
372.0	376.8	75388	4.8	.0	2F4	4.52	.22	4.92	6.09	86.80		1.23	6	22	29	.07		.18			
376.8	378.0	75389	1.2	.0	1D4	3.28	.13	1.10	.52	41.40		.34	19	6	25	.31		.66			
378.0	381.0	75390	3.0	.0	2E7	4.43	.15	.61	.54	19.00		.07	8	25	34	.03		.19			
381.0	383.5	75391	2.5	.0	2F4	4.57	.18	.84	.74	16.20		.17	5	28	33	.04		.14			
383.5	386.0	75392	2.5	.0	****	4.65	.12	6.21	6.02	83.40		.62	6	23	29	.05		.31			
386.0	388.5	75393	2.5	.0	2F4	4.38	.27	8.57	7.95	97.70		1.03	3	19	23	.05		.13			
388.5	391.0	75394	2.5	.0	2F0	4.56	.28	1.47	1.42	20.80		.07	6	23	29	.02		.29			
391.0	393.0	75395	2.0	.0	2F0	4.29	.27	4.36	5.38	49.50		.34	8	18	27	.02		.76			
393.0	408.0	75396	15.0	.0	2F0	4.52	.19	4.47	5.41	54.40		.07	7	21	28	.01		.42			
408.0	410.5	75397	2.5	.0	2C0	2.95	.18	.19	.55	8.70		.07	4	6	11	.32		.04			
410.5	413.0	75398	2.5	.0	2C0	3.26	.30	.31	1.17	16.50		.51	7	11	19	.10		.05			
413.0	415.5	75399	2.5	.0	2C0	3.34	.21	2.05	1.58	36.70		.07	7	11	19	.07		.06			
415.5	418.4	75400	2.9	.0	2C0	3.07	.17	.69	.30	15.60		.21	7	7	15	.19		.14			
418.4	422.0	75401	3.6	.0	2C0	2.80	.12	1.16	.61	22.10		.34	3	5	8	.40		.05			
422.0	423.6	75402	1.6	.0	2E0	3.43	.19	.38	.12	13.40		.07	6	15	22	.08		.04			
423.6	425.5	75403	1.9	.0	2C2	3.45	.20	.07	.10	14.00		.21	5	15	20	.06		.03			
425.5	427.0	75404	1.5	.0	2E4	3.96	.09	1.99	3.29	22.10		.07	6	19	25	.02		.14			
427.0	429.3	75405	2.3	.0	2E4	4.42	.10	1.88	2.87	22.70		.07	3	25	28	.02		.13			

DDH: 81-11 UTM-N: 7991.9 UTM-E: 15396.3 UTM-ELEV: 4024.9 TOTAL DEPTH: 533.0 SECTION: 129
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	---ASSAYS---														
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
286.5	288.0	75410	1.5	.0	2J4	4.12	.34	3.80	7.23	84.60		.14	12	16	28	.38		.30			
288.0	290.0	75411	2.0	.0	2H4	3.87	.35	1.92	3.14	41.70		.07	17	13	31	.02		.12			
290.0	292.5	75412	2.5	.0	2H4	4.21	.50	2.42	5.24	56.30			21	12	34	.04		.22			
302.0	304.0	75414	2.0	.0	2L1	3.10	.26	.88	1.13	27.10		.07	6	7	13	.24		.06			
304.0	309.5	75415	5.5	.0	2C7	3.38	.08	.26	1.04	20.20		.07	2	13	15	.17		.05			
309.5	313.0	75416	3.5	.0	2C7	3.53	.04	1.02	2.41	21.80		.14		14	15	.14		.02			
313.0	314.0	75417	1.0	.0	2F4	4.57	.01	3.52	7.87	37.30		.01		23	24	.14		.03			
314.0	318.0	75418	4.0	.0	2E4	4.42	.08	7.32	11.70	67.80		.07		19	19	.58		.04			
318.0	319.7	75419	1.7	.0	2F4	3.85	.11	2.39	11.60	44.50			2	15	18	3.44		.09			
319.7	321.4	75420	1.7	.0	2L4	3.13	.05	5.96	2.84	51.60			2	6	8	11.85		.08			
342.0	346.0	75422	4.0	.0	2E4	4.36	.34	2.04	2.35	47.00			6	26	33	.13		.21			
346.0	348.0	75423	2.0	.0	2E4	4.56	.17	4.76	4.48	74.60		.07	5	24	29	.06		.21			
357.0	359.5	75425	2.5	.0	2E4	3.76	.30	4.93	2.65	76.20		.07	7	16	23	.20		.14			
359.5	362.0	75426	2.5	.0	2E4	4.02	.15	3.32	1.66	64.40		.07	9	18	28	.10		.16			
362.0	365.5	75427	3.5	.0	2E0	4.58	.14	.89	1.15	19.30		.07	7	25	32	.06		.32			
365.5	369.0	75428	3.5	.0	2E0	4.63	.09	.48	.57	22.10		.07	6	28	34	.04		.25			
369.0	372.5	75429	3.5	.0	2E1	4.12	.36	.89	.55	22.40		.07	3	34	38	.04		.08			
372.5	376.0	75430	3.5	.0	2E1	4.08	.59	1.78	1.83	28.30		.07	3	23	26	.05		.07			
376.0	378.5	75431	2.5	.0	2E14	4.48	.17	2.80	1.42	47.90		.07	6	24	31	.03		.12			
378.5	381.0	75432	2.5	.0	2E1	4.54	.09	.88	.53	18.40		.17	1	29	31	.04		.04			
381.0	384.7	75433	3.7	.0	2E0	4.15	.12	1.32	.73	30.20		.07	4	23	27	.06		.14			
384.7	387.6	75434	2.9	.0	2E0	3.75	.22	.53	1.40	31.10		.07	12	17	29	.08		.20			
387.6	390.4	75435	2.8	.0	2H14	3.92	.12	3.72	3.38	53.80		.07	11	16	27	.05		.11			
390.4	392.0	75436	1.6	.0	1D/2H	3.38	.21	1.58	2.68	25.80		.17	12	9	22	.13		.11			
392.0	395.8	75437	3.8	.0	2H4	4.06	.36	4.45	4.09	44.20		.07	12	16	28	.06		.06			
395.8	397.0	75438	1.2	.0	2F0	4.39	.17	4.04	5.30	37.90		.07	7	19	27	.05		.26			
397.0	400.7	75439	3.7	.0	2F4	3.57	.47	3.64	8.00	36.10		.07	5	19	25	.03		.23			
400.7	404.2	75440	3.5	.0	2C2	4.22	.36	.45	1.83	19.00		.07	7	12	20	.06		.11			
404.2	407.7	75441	3.5	.0	2F0	4.13	.26	2.90	4.90	20.20		.07	6	18	24	.03		.19			
407.7	411.2	75442	3.5	.0	2C2	3.95	.20	1.28	2.14	13.10		.07	7	16	24	.04		.37			
411.2	415.3	75443	4.1	.0	2C2	3.93	.29	.58	1.49	13.70		.07	5	18	23	.03		.15			
415.3	418.4	75444	3.1	.0	2E1	3.92	.40	.29	.51	12.10		.07	3	21	24	.07		.08			
418.4	419.9	75445	1.5	.0	2E0	3.31	.14	.44	1.04	7.50		.14	3	13	16	.22		.04			
419.9	423.9	75446	4.0	.0	2F4	4.37	.11	3.50	9.47	23.60		.07	2	23	26	.01		.07			
423.9	427.8	75447	3.9	.0	2F4	4.26	.14	6.45	12.90	36.70		.07	3	19	23	.02		.06			
427.8	429.5	75448	1.7	.0	2F4	4.31	.08	5.05	10.47	29.20		.07	3	19	23	.01		.05			
429.5	433.0	75449	3.5	.0	2F4	3.58	.04	5.02	10.80	35.50		.07	2	13	15	.06		.04			
433.0	437.5	75450	4.5	.0	2F4	3.71	.04	4.84	9.63	37.30		.07	1	16	18	.05		.03			
437.5	438.7	75451	1.2	.0	2F4	4.29	.15	4.05	8.25	26.80		.07	7	21	28	.03		.14			
438.7	440.7	75452	2.0	.0	2F4	4.35	.03	5.68	12.50	39.80		.07	2	21	23	.03		.04			
440.7	442.0	75453	1.3	.0	2D4	3.90	.02	9.70	12.60	47.60		.07	2	15	17	.05		.03			
442.0	445.0	75454	3.0	.0	2F4	4.47	.03	6.18	10.70	33.60		.07	2	23	25	.03		.03			
445.0	448.0	75455	3.0	.0	2F4	3.50	.06	2.82	8.68	25.80		.07	2	14	17	.07		.03			
448.0	451.7	75456	3.7	.0	2FA	3.49	.07	1.64	7.04	23.60		.07	2	15	17	.05		.02			
451.7	456.8	75457	5.1	.0	2FA	3.46	.08	2.14	7.87	24.90		.07	2	14	17	.04		.02			
456.8	460.8	75458	4.0	.0	2FA	3.83	.05	4.30	7.59	31.10		.07	2	18	21	.02		.02			
460.8	463.5	75459	2.7	.0	2FA	3.51	.13	7.79	15.70	55.70		.17	4	8	13	.06		.02			

DDH: 81-12 UTM-N: 7822.6 UTM-E: 15416.8 UTM-ELEV: 4014.7 TOTAL DEPTH: 488.0 SECTION: 130
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %
206.3	208.0	75462	1.7	.0	2C7	3.12	.20	.17	.18	7.80		.07	6	12	18	.10		.04		
208.0	213.2	75463	5.2	.0	2C7	3.18	.28	.37	.62	10.00		.07	7	11	19	2.27		.05		
213.2	214.9	75464	1.7	.0	2F0	4.30	.04	5.60	8.38	52.30		.07	2	26	29	2.34		.05		
218.0	219.6	75466	1.6	.0	2F7	4.32	.12	8.32	7.81	118.50		.17	7	11	19	19.50		.37		
219.6	221.2	75467	1.6	.0	2E7	3.96	.11	8.73	8.38	126.00		.17	5	17	22	3.91		.26		
262.0	264.6	75470	2.6	.0	2H4	4.11	.28	4.20	6.25	50.10		.07	13	20	34	.20		.19		
264.6	267.0	75471	2.4	.0	2E4	4.29	.27	6.22	9.28	80.90		.07	15	19	34	.02		.18		
267.0	277.0	75472	10.0	.0	2E4	4.32	.24	5.50	8.47	73.70		.07	14	21	35	.01		.13		
277.0	278.0	75473	1.0	.0	2F4	4.67	.08	7.86	13.70	81.50		.07	3	27	30	.01		.04		
278.0	282.0	75474	4.0	.0	2E4	4.45	.29	2.50	4.53	35.50		.07	9	29	39	.01		.14		
282.0	287.0	75475	5.0	.0	2E4	4.35	.34	2.71	5.15	37.30		.07	14	25	39	.01		.14		
287.0	292.0	75476	5.0	.0	2D0	3.23	.10	2.15	4.22	32.00		.07	6	10	16	.16		.07		
292.0	299.8	75477	7.8	.0	2D0	3.52	.21	2.32	3.54	34.50		.07	8	16	24	.07		.08		
299.8	301.1	75478	1.3	.0	2E7	3.71	.22	.57	1.86	17.10		.07	9	23	32	.06		.06		
301.1	303.9	75479	2.8	.0	2A4	3.24	.11	1.96	4.67	34.20		.07	7	10	17	.17		.14		
303.9	309.5	75480	5.6	.0	2H1	3.57	.26	1.75	6.28	27.70		.07	7	16	24	.06		.07		
309.5	314.0	75481	4.5	.0	2F4	4.58	.16	5.34	8.67	42.90		.07	4	29	33	.02		.19		
314.0	318.0	75482	4.0	.0	2E1	3.91	.18	1.30	2.32	19.30		.07	4	27	31	.02		.16		
318.0	322.0	75483	4.0	.0	2E1	4.00	.14	.83	2.36	12.10		.07	4	28	33	.01		.18		
322.0	325.0	75484	3.0	.0	2E4	3.94	.17	2.13	2.69	16.80		.07	5	25	30	.06		.15		
325.0	328.0	75485	3.0	.0	2D4	2.98	.11	2.70	7.93	23.60		.07	3	3	6	.23		.03		
328.0	332.5	75486	4.5	.0	2A4	2.96	.07	1.11	4.49	27.40		.48	3	5	9	.24		.01		
332.5	337.0	75487	4.5	.0	2C0	2.94	.09	.94	2.82	23.30		.07	4	5	9	.21		.03		
337.0	342.0	75488	5.0	.0	2D0	2.96	.05	2.79	5.16	27.70		.17	3	4	7	.04		.02		
342.0	347.0	75489	5.0	.0	2D0	2.92	.04	2.45	3.94	25.20		.14	3	3	6	.20		.02		
347.0	350.0	75490	3.0	.0	2C0	2.90	.07	1.59	1.97	16.20		.07	3	4	8	.21		.03		
350.0	354.9	75491	4.9	.0	2D4	3.10	.06	5.97	4.19	67.50		.21	4	5	10	.14		.03		
354.9	360.7	75492	5.8	.0	2D4	3.23	.06	7.90	6.47	65.30		.21	5	5	10	.18		.08		
360.7	362.3	75493	1.6	.0	2D4	3.39	.13	5.11	13.40	54.10		.82	6	7	13	.13		.04		
362.3	366.7	75494	4.4	.0	2A4	2.93	.04	1.90	4.94	21.80		.69	3	3	7	.24		.01		
366.7	370.0	75495	3.3	.0	2D0	2.98	.03	3.02	5.78	31.40		.89	5	3	8	.10		.04		
370.0	374.0	75496	4.0	.0	2D7	3.08	.06	2.52	4.95	29.50		.82	6	6	12	.22		.05		
374.0	379.5	75497	5.5	.0	2D7	3.02	.05	3.43	4.84	39.80		.75	4	5	9	.09		.03		
379.5	385.0	75498	5.5	.0	2E4	3.92	.18	6.74	14.00	79.90		.07	6	17	23	.04		.04		
385.0	390.0	75499	5.0	.0	2A4	3.02	.01	2.05	8.31	19.30		.84	2	5	8	.24		.02		
390.0	394.0	75500	4.0	.0	2A4	2.91	.02	2.54	4.60	19.60		.69	1	4	6	.18		.02		
394.0	396.4	75501	2.4	.0	2A4	2.91	.06	2.27	5.14	20.20		.07	3	11	14	.23		.02		
396.4	400.0	75502	3.6	.0	2D4	3.38	.09	5.67	11.90	35.50		.07	6		6	.08		.03		
400.0	405.0	75503	5.0	.0	2A4	2.84	.02	2.49	5.05	22.10		.34	2	2	5	.25		.02		
405.0	410.0	75504	5.0	.0	2A4	3.19	.10	1.70	4.98	23.60		.27	6	10	16	.08		.03		
410.0	415.0	75505	5.0	.0	2A4	3.27	.10	1.48	3.83	21.80		.07	5	13	19	.06		.03		
415.0	420.0	75506	5.0	.0	2A0	2.98	.12	1.34	1.99	18.40		.07	4	7	11	.14		.02		
420.0	424.1	75507	4.1	.0	2A0	2.99	.09	.82	1.23	15.60		.62	3	5	8	.18		.01		
424.1	428.2	75508	4.1	.0	2C0	3.07	.17	.41	2.78	9.30		.17	7	8	15	.09		.06		
444.9	447.0	75510	2.1	.0	0Q9	3.73	.10	29.90	3.47	344.60		.96	3	3	6	.08		.05		
447.0	452.4	75511	5.4	.0	2D7	3.27	.39	3.89	4.68	41.10		.07	4	12	16	.09		.02		

DDH: 81-13 UTM-N: 7898.9 UTM-E: 15112.8 UTM-ELEV: 4014.1 TOTAL DEPTH: 504.0 SECTION: 128
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS----						-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
330.9	336.2	75515	5.3	.0 2E4	4.33	.24	7.18	8.17	97.70		.07	13	21	34	.04		.17			
336.2	340.0	75516	3.8	.0 2E0	4.71	.11	2.24	1.67	24.60		.07	4	37	42	.01		.10			
340.0	344.8	75517	4.8	.0 2E4	4.72	.24	2.80	2.60	27.10		.07	4	34	39			.10			
344.8	348.0	75518	3.2	.0 2F4	4.65	.21	4.29	6.08	32.70		.07	4	33	38	.01		.06			
348.0	351.0	75519	3.0	.0 2F4	4.75	.15	5.04	5.89	37.00		.07	2	36	38	.02		.04			
351.0	356.0	75520	5.0	.0 2E4	4.66	.08	3.48	3.99	35.50		.07	3	35	38	.08		.06			
356.0	358.0	75521	2.0	.0 2JF	4.21	.17	2.50	6.15	38.30		.07	7	26	34	.09		.12			
358.0	360.0	75522	2.0	.0 2AC	3.00	.12	.97	1.85	24.30		.07	5	6	11	.31		.08			
360.0	364.0	75523	4.0	.0 2A0	2.80	.09	.93	2.15	20.80		.07	2	3	6	.27		.02			
364.0	369.0	75524	5.0	.0 2A4	2.72	.04	1.35	3.26	16.80		.07	1	1	3	2.01		.03			
417.0	423.0	75527	6.0	.0 2A4	3.09	.12	2.34	4.25	51.00		.41	5	6	12	.20		.04			
423.0	425.4	75528	2.4	.0 2A3	3.03	.10	.77	2.63	28.90		.82	5	7	12	.22		.03			
425.4	428.0	75529	2.6	.0 2A0	2.85	.05	1.15	2.26	21.10		.07	3	3	7	.22		.03			
428.0	434.0	75530	6.0	.0 2A0	2.71	.06	1.34	1.97	14.60		.07	1	2	3	.23		.01			
434.0	440.0	75531	6.0	.0 2A4	2.81	.09	2.84	3.88	26.10		.07	2		2	.13		.02			
440.0	445.0	75532	5.0	.0 2A4	2.91	.12	2.03	4.22	30.80		.07	3	2	6	.11		.02			
445.0	450.0	75533	5.0	.0 2A4	2.79	.09	1.62	3.57	23.00		.14	3	3	6	.14		.03			

DDH: 81-14 UTM-N: 8095.1 UTM-E: 15301.6 UTM-ELEV: 4050.0 TOTAL DEPTH: 641.0 SECTION: 128
 RFE: S2 RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
336.7	341.0	75538	4.3	.0	2C0	2.80	.10	.18	.13	8.40			.07	3	4	8	.36				.03
341.0	346.0	75539	5.0	.0	2C0	2.86	.10	.13	.07	7.50			.07	4	6	10	.17				.03
346.0	351.0	75540	5.0	.0	2C0	3.03	.19	.10	.29	10.00			.07	5	10	15	.14				.05
351.0	356.0	75541	5.0	.0	2C0	3.11	.24	.22	.19	16.50			.07	4	12	17	.07				.05
356.0	361.0	75542	5.0	.0	2C0	3.23	.27	.17	1.17	19.60			.07	5	14	20	.05				.12
361.0	367.2	75543	6.2	.0	2C3	3.18	.17	.10	.44	11.20			.07	4	14	18	.09				.04
367.2	370.5	75544	3.3	.0	2A3	3.30	.13	.08	.22	8.10			.07	3	18	22	.05				.02
370.5	373.5	75545	3.0	.0	2F4	3.63	.10	1.98	10.70	30.80			.07	3	17	21	.03				.07
373.5	376.0	75546	2.5	.0	2F4	3.59	.04	4.43	9.50	52.30			.17	3	16	19	.09				.03
376.0	379.3	75547	3.3	.0	2E1	3.75	.03	.37	2.32	12.80			.07	2	27	29	.11				.03
379.3	382.3	75548	3.0	.0	2F4	3.82	.04	3.27	7.80	35.80			.07	2	24	26	.07				.01
383.1	388.2	75550	5.1	.0	2C3	3.73	.09	.09	.06	8.70			.27	1	28	29	.07				.01
389.5	392.5	75552	3.0	.0	2C3	3.70	.14	.58	2.55	13.10			.41		27	27	.10				.01
392.5	395.0	75553	2.5	.0	2F4	4.31	.05	5.33	8.63	62.20			.14	1	28	30	3.98				.05
414.0	417.0	75555	3.0	.0	2F0	4.43	.12	3.96	2.37	110.40			.21	6	31	38	.17				.25
434.6	435.9	75558	1.3	.0	2F0	4.16	.35	1.68	2.40	32.70			.27	5	29	35	2.10				.08
435.9	440.0	75559	4.1	.0	2G4	4.59	.05	6.57	9.14	92.40			.07	2	12	15	33.80				.05
440.0	445.0	75560	5.0	.0	2G4	4.51	.06	5.51	8.26	76.20			.07	2	14	16	32.95				.07
445.0	450.0	75561	5.0	.0	2G4	4.43	.06	6.26	10.19	89.30			.07	2	9	11	38.26				.05
450.0	454.0	75562	4.0	.0	2G4	4.52	.05	6.08	9.28	90.20			.07	1	9	11	44.12				.03
454.0	457.0	75563	3.0	.0	2G4	4.46	.04	5.64	9.24	92.70			.07	1	8	10	42.69				.03
457.0	460.0	75564	3.0	.0	2J7	3.97	.29	2.85	1.80	53.80			.07	11	24	35	2.01				.17
465.5	467.8	75566	2.3	.0	2E0	4.40	.21	.84	1.00	40.40			.07	9	31	41	2.80				.13
470.0	474.4	75568	4.4	.0	2H9	4.08	.29	.35	1.40	25.20			.07	26	17	44	.04				.04
474.4	479.3	75569	4.9	.0	2H4	4.28	.32	3.47	7.32	53.80			.48	28	13	41	.07				.06
479.3	482.3	75570	3.0	.0	2E7	3.65	.22	.08	.82	12.40			.17	10	28	39	.03				.07
482.3	485.0	75571	2.7	.0	2H9	4.03	.22	.58	2.10	23.90			.41	26	16	42	.03				.04
485.0	488.0	75572	3.0	.0	2C7	3.59	.08	.09	.15	6.80			.21	5	23	29	.03				.03
488.0	491.2	75573	3.2	.0	2C7	3.38	.14	.09	.27	10.00			.27	15	12	28	.02				.02
491.2	496.2	75574	5.0	.0	2H9	4.05	.20	1.06	3.28	24.30			.14	34	8	43	.02				.02
496.2	500.2	75575	4.0	.0	2D3	3.72	.15	1.76	2.80	28.60			.27	8	21	29	.06				.11
500.2	504.5	75576	4.3	.0	2C3	3.51	.35	1.29	1.04	31.70			.07	5	20	26	.03				.09
504.5	508.0	75577	3.5	.0	2H9	3.96	.32	1.44	3.55	34.50			.07	27	11	39	.02				.06
508.0	511.0	75578	3.0	.0	2C3	3.83	.32	.69	.83	16.20			.07	4	27	31	.03				.14
511.0	516.0	75579	5.0	.0	2C3	3.65	.27	.05	.57	13.40			.24	2	26	28	.04				.03
516.0	521.0	75580	5.0	.0	2C3	3.81	.26	.06	.49	7.80			.07	1	29	30	.05				.03
521.0	525.0	75581	4.0	.0	2C3	3.89	.22	.89	1.82	13.70			.07	3	27	31	.05				.13
525.0	528.0	75582	3.0	.0	2C3	3.65	.22	.10	.54	10.00			.07	2	26	28	.05				.04
528.0	532.0	75583	4.0	.0	2F4	4.04	.10	4.31	9.83	27.10			.07	3	24	28	.20				.08
532.0	536.0	75584	4.0	.0	2F4	4.52	.03	5.82	11.20	37.00			.07	2	30	32	.05				.03
536.0	540.0	75585	4.0	.0	2F4	4.37	.06	7.17	13.90	33.30			.07	3	26	29	.04				.04
540.0	543.4	75586	3.4	.0	2F4	4.59	.01	6.29	12.50	35.50			.14	1	30	32	.04				.02
543.4	544.4	75587	1.0	.0	2F4	3.68	.01	3.95	13.00	24.30			.07	1	18	19	.15				.01
544.4	549.0	75588	4.6	.0	2F4	4.50	.03	7.48	15.50	39.50			.41	2	26	29	.05				.03
549.0	554.0	75589	5.0	.0	2F4	4.39	.04	7.13	13.50	39.80			.07	2	26	29	.04				.02

DDH: 81-14 UTM-N: 8095.1 UTM-E: 15301.6 UTM-ELEV: 4050.0 TOTAL DEPTH: 641.0 SECTION: 128
 RFE: S2 RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
554.0	559.0	75590	5.0	.0	2D3	3.40	.06	.57	3.61	10.00		.07	2	26	29	.11		.03			
559.0	564.0	75591	5.0	.0	2A3	3.52	.02	.46	1.69	13.10		.07	1	21	23	.10		.02			
564.0	569.0	75592	5.0	.0	2A3	3.39	.03	.06	.35	3.70		.07	1	21	22	.10		.01			
569.0	572.4	75593	3.4	.0	2A34	3.41	.26	2.43	6.34	26.10		.51	5	15	20	.06		.05			

DDH: 81-15 UTM-N: 8084.3 UTM-E: 15504.8 UTM-ELEV: 4100.8 TOTAL DEPTH: 685.0 SECTION: 129
 RFE: S2 RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
477.5	482.0	75598	4.5	.0	2D0	3.95	.08	5.33	8.69	50.70		.41	3	22	25	.70		.05			
482.0	485.7	75599	3.7	.0	2D0	3.72	.03	2.60	6.75	26.40		.27	1	21	23	.91		.02			
485.7	488.0	75600	2.3	.0	2CE	3.74	.06	2.02	2.81	34.80		.48	4	19	23	5.33		.10			
488.0	491.4	75601	3.4	.0	2CE4	3.37	.12	1.76	1.98	25.80		.62	6	15	21	.22		.14			
493.2	497.0	75603	3.8	.0	2CE4	3.65	.12	2.34	3.53	44.50		1.20	3	16	19	8.71		.10			
497.0	500.7	75604	3.7	.0	2CE	3.22	.17	1.01	1.00	20.80		1.23	3	14	18	.29		.06			
500.7	503.7	75605	3.0	.0	2EF	3.76	.15	2.75	3.78	27.70		.07		19	19	.07		.18			
503.7	506.6	75606	2.9	.0	2EF	3.91	.14	4.92	6.85	41.10		.17	8	20	29	.06		.12			
506.6	510.0	75607	3.4	.0	2DE	3.43	.11	3.63	6.45	40.70		.27	8	13	21	.20		.11			
510.0	516.0	75608	6.0	.0	2CE	3.33	.16	.60	3.18	16.20		.51	6	16	23	.23		.08			
516.0	521.0	75609	5.0	.0	2DE	3.96	.26	2.40	3.21	30.50		.07	5	25	31	.01		.19			
521.0	526.0	75610	5.0	.0	2DE	4.29	.25	4.00	4.94	35.10		.07	6	28	34	.01		.25			
526.0	530.0	75611	4.0	.0	2CE	3.64	.23	.45	1.08	12.80		.07	4	23	28	.01		.18			
530.0	533.0	75612	3.0	.0	2CE	3.46	.22	.98	2.17	10.90		.17	5	19	24	.04		.16			
533.0	534.0	75613	1.0	.0	1D9	3.47	.07	.95	3.11	19.30		.07	2	19	21	.08		.06			
534.0	537.0	75614	3.0	.0	2E1	3.87	.18	.69	1.73	10.30		.17	3	27	31	.02		.11			
537.0	540.0	75615	3.0	.0	2E1	4.05	.33	.41	1.69	13.10		.27	5	29	34	.01		.17			
540.0	542.0	75616	2.0	.0	2C9	3.50	.43	.80	1.75	13.40		.27	4	21	25	.01		.10			
542.0	545.3	75617	3.3	.0	2EF	4.27	.09	4.20	8.49	19.00		.14	4	28	32	.01		.08			
545.3	547.7	75618	2.4	.0	2EF	4.18	.05	4.95	12.00	18.00		.07	3	24	27	.06		.04			
547.7	552.0	75619	4.3	.0	2EF	3.49	.08	5.54	10.70	33.00		.07	3	12	15	.06		.04			
552.0	555.6	75620	3.6	.0	2F4	4.59	.02	6.72	10.40	30.20		.07	2	31	33	.03		.02			

DDH: 81-16 UTM-N: 7843.8 UTM-E: 15662.7 UTM-ELEV: 4013.1 TOTAL DEPTH: 518.0 SECTION: 131
 RFE: S2 RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
218.7	220.6	75626	1.9	.0	2D4	3.30	.53	5.72	4.59	235.10		.31	5	9	15	.70		.10			
220.6	222.5	75627	1.9	.0	2E4	3.70	.57	1.50	4.57	65.90		.17	9	19	29	.63		.10			
222.5	224.6	75628	2.1	.0	2D0	3.73	.15	1.09	4.35	33.30		.62	2	23	26	.07		.04			
224.6	226.7	75629	2.1	.0	2D4	3.71	.13	3.64	8.59	74.30		.41	4	19	23	.16		.15			
226.7	228.8	75630	2.1	.0	2D0	3.60	.09	1.65	4.52	38.60		.07	1	22	24	.03		.06			
228.8	231.3	75631	2.5	.0	2E4	3.86	.21	8.33	12.40	84.60		1.10	8	13	22	.07		.39			
231.3	233.4	75632	2.1	.0	2D0	3.72	.19	2.10	6.32	32.00		.41	3	21	25	.04		.13			
233.4	234.5	75633	1.1	.0	2F0	3.85	.04	2.36	5.69	32.70		.62	1	25	26	.02		.01			
234.5	236.9	75634	2.4	.0	2D0	3.76	.04	1.65	6.47	23.90		.17	1	24	25	.01		.02			
236.9	239.3	75635	2.4	.0	2D0	3.76	.07	3.39	5.99	63.10		.27	1	23	24	.06		.03			
239.3	243.5	75636	4.2	.0	2EF/4	4.38	.17	7.56	5.58	163.60		.96	2	29	32	.03		.15			
252.6	253.3	75638	.7	.0	2E0	3.98	.27	.17	.38	13.70		.41	5	29	34	.42		.16			
254.8	257.3	75640	2.5	.0	2E8	4.54	.20	1.03	.30	33.60		.07	6	34	41	.04		.32			
257.3	259.8	75641	2.5	.0	2E8	4.45	.23	.69	.32	29.50		.07	5	35	41	.04		.20			
259.8	262.3	75642	2.5	.0	2E8	4.40	.16	1.02	.36	30.80		.07	5	34	40	.04		.27			
262.3	264.8	75643	2.5	.0	2E8	4.56	.22	1.34	.88	48.50		.14	5	35	40	.02		.34			
264.8	267.3	75644	2.5	.0	2E84	4.59	.27	2.99	2.41	84.30		.17	6	34	40	.06		.39			
267.3	269.8	75645	2.5	.0	2E8	4.52	.14	2.39	1.45	55.10		.17	6	34	40	.04		.36			
269.8	272.3	75646	2.5	.0	2E8	4.45	.10	.05	.17	8.40		.07	5	35	41	.07		.22			
272.3	274.8	75647	2.5	.0	2E8	4.42	.10	.04	.15	6.20		.07	6	35	41	.05		.25			
274.8	277.3	75648	2.5	.0	2E8	4.43	.23	1.21	.20	35.50		.07	5	34	40	.07		.36			
277.3	279.4	75649	2.1	.0	2H9	4.15	.77	.61	.15	22.10		.07	48	4	52	.07		.20			
279.4	281.4	75650	2.0	.0	2H4	4.33	.77	3.10	2.89	85.80		.07	2	5	8	.06		.35			
281.4	283.4	75651	2.0	.0	2C2	4.31	.25	.24	.16	13.40		.17	4	40	44	.07		.20			
283.4	286.2	75652	2.8	.0	2E8	4.43	.16	.14	.22	17.40		.07	3	36	40	.08		.20			
286.2	289.0	75653	2.8	.0	2E84	4.56	.20	3.17	2.67	52.60		.17	6	33	39	.01		.39			
289.0	291.8	75654	2.8	.0	2E8	4.50	.28	.80	.29	63.40		.10	7	34	41	.02		.38			
291.8	294.5	75655	2.7	.0	2E8	4.48	.13	1.58	1.17	70.30		.07	5	34	39	.02		.36			
294.5	296.7	75656	2.2	.0	2F4	4.45	.36	8.15	5.82	143.40		.82	6	27	33	.18		.36			
296.7	298.9	75657	2.2	.0	2F4	4.55	.34	7.51	5.35	143.10		.62	3	31	35	.11		.24			
298.9	300.7	75658	1.8	.0	2E0	4.62	.33	1.68	1.50	50.40		.07	6	34	41	.01		.39			
300.7	301.9	75659	1.2	.0	2F4	4.48	.32	7.35	9.35	121.00		.55	9	23	32	.03		1.19			
301.9	304.1	75660	2.2	.0	2E4	4.44	.30	3.50	1.95	94.20		.69	6	31	38	.01		.51			
304.1	307.6	75661	3.5	.0	2F0	4.50	.16	4.96	2.08	76.80		1.20	4	32	36	.04		.24			
307.6	310.4	75662	2.8	.0	2E4	4.42	.32	4.30	2.28	64.10		1.51	1	34	35	.03		.03			
310.4	313.2	75663	2.8	.0	2E4	4.23	.06	3.26	1.63	87.40		.55	1	30	32	.03		.06			
313.2	315.9	75664	2.7	.0	2E0	3.69	.15	1.56	1.64	87.40		.17	1	24	26	.07		.04			
315.9	318.2	75665	2.3	.0	1D0	3.08	.08	.75	.75	83.00		.33	2	10	13	.21		.06			
318.2	320.6	75666	2.4	.0	2E4	4.07	.28	1.68	2.81	69.00		.17	4	28	32	.03		.20			
320.6	323.0	75667	2.4	.0	2E4	4.23	.30	2.01	2.12	66.90		.07	4	30	35	.01		.20			
323.0	326.1	75668	3.1	.0	2E0	3.86	.28	.62	.63	28.30		.51	3	27	31	.13		.17			
326.1	329.2	75669	3.1	.0	2E0	3.72	.24	.76	1.56	34.20		.27	3	23	26	.09		.16			
329.2	332.0	75670	2.8	.0	2E4	3.49	.18	1.16	3.30	32.00		.07	2	19	21	.09		.18			
332.0	334.8	75671	2.8	.0	2E4	3.57	.15	1.46	3.25	33.00		.07	3	18	22	.10		.11			
334.8	337.5	75672	2.7	.0	2E4	3.99	.12	2.42	5.57	28.60		.07	4	26	30	.07		.11			

DDH: 81-18 UTM-N: 7845.7 UTM-E: 15256.9 UTM-ELEV: 4012.4 TOTAL DEPTH: 478.0 SECTION: 129
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
226.0	229.6	75687	3.6	.0	2C0	3.31	.17	.07	.14	.90		.34	2	18	21	.03		.02			
229.6	230.8	75688	1.2	.0	2E0	2.94	.22	.01	.09	.60		.07	3	30	33	.02		.04			
230.8	234.0	75689	3.2	.0	2C0	3.22	.09	.03	.07	5.60		.17	2	16	19	.07		.03			
234.0	237.2	75690	3.2	.0	2C0	3.63	.09	.09	.42	.30		.07	3	24	28	.06		.05			
237.2	241.0	75691	3.8	.0	2A4F	3.24	.09	.84	10.06	8.70		.07	2	11	14	.09		.04			
241.0	246.0	75692	5.0	.0	2A4F	3.33	.08	1.87	5.70	8.70		.48	2	15	17	.06		.02			
246.0	251.0	75693	5.0	.0	2A4F	3.35	.12	1.59	3.70	13.10		.69	2	16	18	.10		.02			
251.0	252.8	75694	1.8	.0	2F4	4.26	.15	5.65	7.57	79.30		.41	6	16	22	13.86		.28			
252.8	255.0	75695	2.2	.0	2F4	4.57	.20	6.54	5.63	107.60		.82	6	22	29	9.92		.45			
255.0	258.6	75696	3.6	.0	2F4	4.60	.13	6.43	5.85	102.00		.69	6	23	29	10.14		.51			
258.6	259.0	75697	.4	.0	2H0	4.25	.45	1.31	6.11	112.60		.96	12	20	32	2.16		.73			
286.5	288.5	75699	2.0	.0	2D0	3.29	.18	3.84	4.19	74.30		.27	6	8	15	5.17		.25			
288.5	293.0	75700	4.5	.0	2H4	4.21	.33	4.49	7.08	78.10		.17	15	20	35	.37		.25			
293.0	297.0	75701	4.0	.0	2E0	4.70	.16	1.19	1.87	17.40		.07	4	37	42	.07		.07			
297.0	300.0	75702	3.0	.0	2E0	4.82	.03	2.80	3.81	33.60		.07	1	38	39	2.27		.02			
300.0	304.2	75703	4.2	.0	2E0	4.73	.09	1.32	1.48	19.90		.07	3	40	43	.05		.05			
304.2	308.4	75704	4.2	.0	2EF	4.73	.13	3.10	4.98	36.40		.07	3	37	40	.06		.06			
308.4	309.9	75705	1.5	.0	2F4	4.82	.08	4.68	7.34	42.30		.07	1	35	37	.12		.04			
309.9	311.7	75706	1.8	.0	2E4	4.83	.15	2.41	3.57	22.70		.07		40	41	.17		.01			
311.7	314.0	75707	2.3	.0	2F0	4.87	.12	4.24	5.00	43.20		.07	1	38	39	.25		.02			
314.0	318.5	75708	4.5	.0	2H4	4.25	.41	2.98	5.05	38.60		.07	19	21	40	.09		.14			
318.5	321.3	75709	2.8	.0	2EF4	4.61	.26	5.21	8.20	64.10		.07	5	30	36	.45		.11			
321.3	323.4	75710	2.1	.0	2E8	4.50	.39	.89	1.69	17.70		.07	7	34	42	.10		.18			
323.9	326.9	75712	3.0	.0	2E8	4.56	.45	1.08	2.68	20.20		.07	5	36	41	.06		.12			
326.9	329.0	75713	2.1	.0	2E84	4.55	.24	.93	3.75	14.30		.07	6	34	41	.05		.16			
329.0	331.4	75714	2.4	.0	2H4	4.27	.57	3.99	5.64	41.10		.07	20	9	30	.09		.08			
331.4	335.0	75715	3.6	.0	2J7	3.86	.58	2.57	5.14	28.00		.07	13	26	40	.06		.10			
335.0	339.0	75716	4.0	.0	2D0	3.26	.16	1.40	4.23	24.30		.07	6	6	12	.20		.06			
339.0	343.0	75717	4.0	.0	2C0	2.94	.15	1.14	2.85	25.50		.07	6	2	8	.57		.07			
343.0	348.0	75718	5.0	.0	2D0	2.71	.03	1.34	2.93	26.10		.07	1	1	3	.24		.03			
348.0	351.0	75719	3.0	.0	2D0	2.82	.04	4.00	2.22	74.30		.17	1	1	3	.22		.04			
351.0	354.3	75720	3.3	.0	2C0	2.74	.05	.95	2.13	24.30		.41	1	1	3	.24		.03			
354.3	359.0	75721	4.7	.0	2D0	2.62	.04	1.21	2.79	28.90		.27	1	1	3	.22		.03			
359.0	364.0	75722	5.0	.0	2A4	2.63	.03	1.36	2.84	22.70		.17	1	1	2	.26		.02			
364.0	369.5	75723	5.5	.0	2A0	2.70	.04	.88	1.90	16.80		.14	2	1	3	.40		.03			
369.5	372.2	75724	2.7	.0	2A0	2.67	.04	.88	1.73	15.20		.17	2	2	4	.36		.04			
372.2	377.0	75725	4.8	.0	2A0	2.72	3.11	1.09	1.63	24.90		.17	2	2	5	.25		.04			
377.0	381.0	75726	4.0	.0	2A0	2.82	.18	.85	.65	46.00		.27	3	4	8	.18		.04			
381.0	384.0	75727	3.0	.0	2A0	2.97	.26	.42	.39	30.20		.07	4	6	10	.11		.04			
384.0	388.0	75728	4.0	.0	2A4	2.96	.08	1.73	4.36	28.60		.07	2	5	7	.31		.03			
388.0	393.7	75729	5.7	.0	2A4	2.94	.08	2.26	2.61	25.80		.48	1	5	7	.26		.03			
393.7	398.7	75730	5.0	.0	2A0	2.73	.04	1.10	2.82	20.20		.07	1	2	3	.43		.03			
398.7	402.0	75731	3.3	.0	2A0	2.84	.03	1.14	3.53	20.50		.62	1	3	4	.17		.03			
402.0	406.0	75732	4.0	.0	2A4	2.71	.04	1.68	3.08	19.30		.17	1	2	3	.19		.03			
406.0	408.9	75733	2.9	.0	2D0	2.86	.06	1.25	3.87	21.50		.96	2	3	5	.23		.03			
408.9	414.0	75734	5.1	.0	2A4	2.66	.03	1.36	3.40	17.70		.48	1	1	2	.16		.02			
414.0	419.0	75735	5.0	.0	2A4	2.73	.02	1.51	3.19	18.00		.27				.18		.01			
419.0	424.0	75736	5.0	.0	2A4	2.72	.02	1.73	3.92	27.40		.75	1		1	.16		.02			
424.0	428.0	75737	4.0	.0	2A4	2.72	.04	1.35	3.21	26.40		.96	1	1	3	.23		.03			

DDH: 81-18 UTM-N: 7845.7 UTM-E: 15256.9 UTM-ELEV: 4012.4 TOTAL DEPTH: 478.0 SECTION: 129
RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS----				-----ASSAYS-----																
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
428.0	430.0	75738	2.0	.0	2D0	2.85	.08	1.38	4.92	30.20		.55	2	1	4	.19		.04		

DDH: 81-19 UTM-N: 8102.2 UTM-E: 15699.7 UTM-ELEV: 4101.3 TOTAL DEPTH: 624.0 SECTION: 130
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
396.0	398.7	75744	2.7	.0	2D0	4.15	.18	3.91	5.58	41.10		.17	5	27	33	.18		.08			
398.7	401.4	75745	2.7	.0	2D4	4.14	.18	1.97	19.51	24.60		.07	7	29	37	.04		.28			
401.4	403.7	75746	2.3	.0	2E82	4.42	.13	.92	2.48	17.10		.07	8	32	41	.04		.54			
403.7	406.0	75747	2.3	.0	2E84	4.58	.08	2.33	3.55	21.80		.07	6	34	41	.04		.35			
406.0	412.0	75748	6.0	.0	2F84	4.50	.33	5.15	7.04	62.50		.07	6	29	36	.03		.44			
412.0	414.4	75749	2.4	.0	2D0	4.11	.19	3.36	3.54	60.30		.82	1	30	32	.03		.05			
414.4	416.9	75750	2.5	.0	2C0	3.64	.80	2.41	.51	89.90	1.37	1	24	25	.03		.02				
416.9	419.7	75751	2.8	.0	2FE4	4.65	.20	5.64	5.07	74.60	.41	2	34	37	.03		.04				
419.7	422.1	75752	2.4	.0	2D0	3.98	.11	3.86	6.14	36.70	.27	1	26	27	.03		.02				
422.1	424.5	75753	2.4	.0	2D0	4.13	.34	2.74	4.76	37.60	.51	1	31	32	.05		.02				
424.5	426.9	75754	2.4	.0	2D0	4.19	.13	2.27	5.94	28.00	.69	1	30	31	.03		.02				
426.9	429.3	75755	2.4	.0	2D0	4.00	.10	3.55	2.82	44.50	1.20	1	28	29	.05		.01				
429.3	431.7	75756	2.4	.0	2D0	4.24	.06	2.58	5.20	33.00	.69	1	31	33	.06		.01				
431.7	434.1	75757	2.4	.0	2D0	4.11	.07	2.49	4.27	26.70	.34	1	30	31	.05		.01				
434.1	436.6	75758	2.5	.0	2C0	3.67	.19	.47	1.39	12.40	.48		26	27	.06		.01				
436.6	439.1	75759	2.5	.0	2D0	3.81	.09	2.48	3.56	24.90	.27		26	27	.06		.01				
439.1	441.8	75760	2.7	.0	2DE4	4.18	.09	6.42	10.12	67.80	.69	2	25	27	.03		.08				
441.8	444.5	75761	2.7	.0	2DE4	4.44	.02	7.68	12.10	63.80	.17	2	26	29	.03		.09				
444.5	447.0	75762	2.5	.0	2D0	3.63	.20	1.91	2.64	20.80	.34	2	22	25	.04		.15				
447.0	449.4	75763	2.4	.0	2C0	3.61	.17	1.26	2.19	23.00	.51	3	22	26	.06		.12				
449.4	451.5	75764	2.1	.0	2D0	3.53	.40	2.65	2.81	34.20	.69	4	19	23	.05		.13				
451.5	453.3	75765	1.8	.0	2E1	4.43	.06	.27	.52	4.70	.86	2	38	40	.05		.03				
453.3	456.0	75766	2.7	.0	2C0	3.89	.08	1.29	1.84	16.80	.55	1	28	30	.05		.03				
456.0	458.7	75767	2.7	.0	2C0	3.92	.10	.25	1.11	3.10	.07	1	30	32	.03		.02				
458.7	461.4	75768	2.7	.0	2D4	4.41	.15	7.60	4.38	44.50	.07	2	30	32	.03		.07				
461.4	464.2	75769	2.8	.0	2D0	4.08	.26	3.42	1.39	28.30	.07	1	31	33	.01		.06				
464.2	465.2	75770	1.0	.0	2D4	3.95	.41	6.43	5.42	46.70	.07	10	17	28	.02		.58				
465.2	467.8	75771	2.6	.0	2D0	4.07	.18	3.85	3.50	29.20	.07	2	29	31	.02		.13				
467.8	470.4	75772	2.6	.0	2C0	4.12	.31	1.70	1.25	14.30	.07	1	32	33	.02		.06				
470.4	473.0	75773	2.6	.0	2C0	4.02	.24	.09	.55	7.50	.07	1	32	33	.01		.03				
473.0	475.6	75774	2.6	.0	2C0	4.41	.21	.07	.42	5.90	.07	1	39	40	.01		.04				
475.6	478.3	75775	2.7	.0	2C0	4.21	.20	.05	.40	2.80	.07	2	34	36	.02		.09				
478.3	481.0	75776	2.7	.0	2D0	4.13	.27	2.02	2.00	18.70	.07	2	32	34	.01		.08				
481.0	484.0	75777	3.0	.0	2D2	4.00	.23	2.31	2.85	21.80	.07	4	27	32	.02		.15				
484.8	486.3	75779	1.5	.0	2E8	4.41	.47	1.97	2.13	21.80	.07	6	33	39	.02		.27				
486.3	487.5	75780	1.2	.0	2F4	4.41	.19	10.24	9.42	67.50	.07	6	23	29	.03		.43				
487.5	490.2	75781	2.7	.0	2D8	4.17	.22	1.07	3.15	9.00	.07	5	29	35	.01		.24				
490.2	492.8	75782	2.6	.0	2C8	4.03	.28	1.18	1.98	12.80	.07	5	27	33	.02		.22				
492.8	495.4	75783	2.6	.0	2C8	4.07	.22	.13	.72	5.30	.07	5	30	36	.03		.20				
495.4	498.0	75784	2.6	.0	2C8	4.01	.33	.78	1.22	15.90	.07	4	29	34	.03		.18				
498.0	500.7	75785	2.7	.0	2D0	3.85	.22	2.25	3.60	14.00	.07	4	24	28	.01		.32				
500.7	503.4	75786	2.7	.0	2D0	3.69	.12	2.24	5.54	14.60	.07	2	22	24	.10		.04				
503.4	506.1	75787	2.7	.0	2C0	3.51	.18	.50	3.10	18.40	.07	2	21	23	.05		.13				
506.1	508.8	75788	2.7	.0	2C0	3.81	.25	.37	.75	8.70	.07	2	28	30	.02		.13				
508.8	511.5	75789	2.7	.0	2C0	3.74	.19	.03	.76	7.50	.07	1	27	29	.03		.09				
511.5	513.6	75790	2.1	.0	2C3	3.66	.20	.08	.32	2.80	.07	1	27	28	.05		.02				
513.6	515.8	75791	2.2	.0	2C3	3.71	.38	.15	.66	10.90	.07	1	26	28	.04		.06				
515.8	518.0	75792	2.2	.0	2C3	3.20	.51	.94	1.96	12.40	.07	1	33	35	.02		.05				
518.0	520.2	75793	2.2	.0	2C3	4.24	.29	.16	1.29	2.20	.07	1	34	36	.01		.04				
520.2	522.3	75794	2.1	.0	2C3	3.92	.36	.66	1.01	10.90	.07	1	30	32	.02		.05				

DDH: 81-19 UTM-N: 8102.2 UTM-E: 15699.7 UTM-ELEV: 4101.3 TOTAL DEPTH: 624.0 SECTION: 130
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----						-----ASSAYS-----																	
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.		
522.3	524.5	75795	2.2	.0	2C3	4.13	.48	.35	.84	8.70		.07	1	34	35	.04		.01					
524.5	526.6	75796	2.1	.0	2C3	4.05	.24	.23	.10	9.30		.07		33	34	.04		.01					
526.6	528.7	75797	2.1	.0	2C3	4.06	.18	1.22	.93	9.00		.07	2	31	34	.02		.06					
528.7	530.8	75798	2.1	.0	2C3	4.25	.16	.47	1.18	4.00		.07	2	34	37	.02		.06					
530.8	533.1	75799	2.3	.0	2F4	3.74	.09	3.19	8.13	10.30		.07	2	22	24	.07		.03					
533.1	535.4	75800	2.3	.0	2F4	3.82	.08	5.00	10.20	12.10		.17	2	21	23	.04		.03					
535.4	537.5	75801	2.1	.0	2D0	3.58	.05	2.04	5.55	15.90		.07	1	20	22	.11		.03					
537.5	540.7	75802	3.2	.0	2D4	3.51	.12	4.98	12.80	33.90		.07	4	11	16	.10		.05					
540.7	543.8	75803	3.1	.0	2D0	3.12	.09	1.78	2.55	15.90		.07	5	9	14	.16		.04					
543.8	546.9	75804	3.1	.0	2L4	2.93	.10	1.23	4.01	19.00		.34	4	4	8	.24		.05					
546.9	550.0	75805	3.1	.0	2L4	2.97	.11	1.72	4.42	24.30		.55	3	3	7	.34		.05					
550.0	553.1	75806	3.1	.0	2L3	2.82	.07	1.44	1.50	22.70		.27	1	2	3	2.03		.01					
553.1	556.2	75807	3.1	.0	2L3	2.76	.05	1.22	1.81	19.00		.27	1	1	2	.46		.01					
556.2	559.2	75808	3.0	.0	2L3	2.78	.04	1.51	2.53	16.50		.41	1	1	2	.47		.01					
559.2	562.2	75809	3.0	.0	2L3	2.74	.04	1.05	2.20	23.60		.69		1	2	.47		.01					
562.2	565.9	75810	3.7	.0	2A0	2.73	.07	1.29	2.49	19.90		.55	1	1	3	.40		.01					
565.9	568.9	75811	3.0	.0	2L4	2.90	.14	1.08	3.47	20.20		.27	2	4	7	.31		.03					
568.9	571.9	75812	3.0	.0	2L1	2.76	.05	1.05	2.74	14.90		.07	1	1	2	.50		.02					
571.9	574.8	75813	2.9	.0	2L1	2.80	.04	.46	.66	8.70		.07	2	2	5	.38		.09					
574.8	577.7	75814	2.9	.0	2L1	2.78	.11	.55	1.38	11.20		.07	2	2	4	.40		.02					

DDH: 81-20 UTM-N: 7733.0 UTM-E: 15533.0 UTM-ELEV: 4017.9 TOTAL DEPTH: 421.0 SECTION: 131
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
221.8	224.5	75820	2.7	.0	2H34	3.79	.38	4.53	5.19	73.10			.07	12	16	28	2.27		.16		
224.5	227.3	75821	2.8	.0	2H34	4.36	.29	5.12	8.90	59.70			.07	31	9	41	.07		.13		
227.3	229.8	75822	2.5	.0	2E74	4.28	.24	5.32	8.47	61.30			.07	16	19	36	.02		.13		
229.8	232.4	75823	2.6	.0	2E74	4.30	.35	4.76	8.19	61.60			.07	14	21	36	.02		.15		
232.4	236.7	75824	4.3	.0	2H34	4.29	.28	5.04	8.93	65.90			.07	30	9	40			.12		
236.7	239.9	75825	3.2	.0	2F4	4.38	.05	5.10	7.75	53.50			.07	2	30	33	.01		.05		
239.9	246.3	75826	6.4	.0	2F4	4.66	.03	6.96	13.70	58.80			.07	2	29	31	.02		.02		
246.3	249.5	75827	3.2	.0	2F4	4.69	.03	8.24	12.60	67.50			.07	1	30	32	.01		.02		
249.5	252.7	75828	3.2	.0	2F4	4.74	.06	3.59	8.06	28.60			.07	1	36	37	.01		.02		
252.7	255.9	75829	3.2	.0	2F4	4.54	.11	3.31	6.78	31.70			.07	3	32	36	.01		.10		
255.9	257.3	75830	1.4	.0	2F4	4.26	.34	4.82	8.94	50.40			.07	29	9	38	.01		.27		
257.3	260.5	75831	3.2	.0	2F4	4.67	.23	6.23	12.20	50.40			.07	3	29	33	.01		.08		
260.5	263.6	75832	3.1	.0	2F4	4.64	.10	4.10	7.87	41.10			.07	3	33	36	.01		.07		
263.6	264.6	75833	1.0	.0	2H4	4.30	.40	3.92	7.06	39.20			.07	30	11	41	.21		.10		
264.6	267.6	75834	3.0	.0	2FE	4.60	.11	1.98	5.66	21.80			.07	3	34	38	.01		.08		
267.6	270.2	75835	2.6	.0	2D5	3.20	.40	.54	4.82	11.80			.07	5	11	16	.23		.07		
270.2	272.8	75836	2.6	.0	2D5	3.07	.18	2.18	6.88	27.70			.07	4	6	10	.31		.05		
272.8	275.4	75837	2.6	.0	2D5/4	2.98	.08	2.79	8.26	34.20			.34	3	4	7	.22		.03		
275.4	277.9	75838	2.5	.0	2D5	2.99	.07	2.24	4.78	30.50			.27	3	5	9	.21		.03		
277.9	281.4	75839	3.5	.0	2A14	3.00	.10	1.73	4.72	28.00			.27	4	6	10	.16		.02		
281.4	284.9	75840	3.5	.0	2A14	2.92	.07	.97	3.74	18.00			.07	3	5	8	.16		.02		
284.9	288.4	75841	3.5	.0	2A14	2.92	.05	3.39	6.63	39.80			.14	2	3	6	.15		.02		
288.4	291.9	75842	3.5	.0	2A14	2.97	.07	1.47	4.78	29.60			.27	3	6	10	.15		.03		
291.9	295.2	75843	3.3	.0	2A4	2.86	.06	1.75	4.50	28.00			.07	4	3	7	.21		.06		
295.2	298.5	75844	3.3	.0	2A4	2.77	.05	1.69	4.67	29.60			.27	2	2	4	.17		.03		
298.5	301.8	75845	3.3	.0	2A4	2.77	.03	1.70	3.33	21.50			.34	1	2	4	.15		.03		
301.8	305.2	75846	3.4	.0	2A4	2.83	.07	1.19	2.53	25.80			.27	2	5	7	.14		.03		
305.2	308.6	75847	3.4	.0	2A4	2.87	.05	1.27	3.46	21.50			.27	4	2	7	.29		.05		
308.6	312.0	75848	3.4	.0	2A4	2.74	.04	1.54	3.83	23.00			.41	2	2	4	.18		.03		
312.0	314.4	75849	2.4	.0	2A0	2.76	.05	1.28	1.38	25.80			.07	3	2	5	.28		.04		
314.4	316.7	75850	2.3	.0	2A0	2.74	.05	1.16	1.24	21.20			.17	3	2	5	2.02		.05		
316.7	319.0	75851	2.3	.0	2A4	2.74	.04	2.20	2.06	31.10			.48	2	2	5	.24		.03		
319.0	324.9	75852	5.9	.0	2A0	2.59	.02	.70	1.02	9.60			.07	1		2	2.36		.02		
324.9	327.2	75853	2.3	.0	2A0	2.65	.02	.92	2.47	12.40			.07	1		2	.29		.07		
327.2	328.5	75854	1.3	.0	2A0	2.69	.03	1.14	2.83	21.20			.07	2	1	3	2.02		.02		
335.0	336.0	75856	1.0	.0	2A0	2.86	.12	.32	.58	12.10			.07	3	6	9	.10		.02		

DDH: 81017 UTM-N: 7734.0 UTM-E: 15529.4 UTM-ELEV: 4017.7 TOTAL DEPTH: 248.0 SECTION:
 RFE: RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS----						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
210.0	212.9	75677	2.9	.0	****	2.72	.02	.40	.51	.80		.07	1	2	4	3.27		.05			
226.4	227.6	75679	1.2	.0	****	3.08	.10	1.14	2.53	18.70		.07	5	10	15	2.69		.06			
227.6	229.6	75680	2.0	.0	****	4.32	.22	4.61	7.98	52.90		.07	14	25	40	.07		.10			
229.6	232.6	75681	3.0	.0	****	3.14	.03	.72	3.07	12.10		.07	1	15	16	.04		.02			
232.6	238.8	75682	6.2	.0	****	4.63	.03	5.84	9.85	46.30		.07	1	36	38	.01		.04			
238.8	245.0	75683	6.2	.0	****	4.73	.11	5.31	9.26	37.90		.07	1	38	40	.01		.03			
245.0	248.0	75684	3.0	.0	****	4.73	.03	5.97	9.69	42.30		.07	1	33	35	.01		.02			

DDH: 82F-01 UTM-N: 8881.5 UTM-E: 15313.2 UTM-ELEV: 4071.3 TOTAL DEPTH: 903.0 SECTION: 124
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
532.5	537.6	82001	5.1	5.1	2C07	3.57	.26	.54	2.07	11.82		.10	5	19	25	.13		.08			
537.6	542.7	82002	5.1	5.1	2C07	3.33	.18	.12	1.81	8.09		.04	8	12	21	.02		.03			
542.7	547.8	82003	5.1	5.1	2C07	3.57	.19	.23	1.81	8.09		.10	8	16	25	.01		.06			
547.8	552.9	82004	5.1	5.1	2C07	3.57	.14	.32	1.29	7.78		.07	6	17	23	.06		.03			
552.9	556.7	82005	3.8	3.8	2D4	3.45	.05	4.08	12.40	19.91		.10	3	11	15	.10		.02			
556.7	560.7	82006	4.0	4.0	2CE4	4.22	.06	2.48	6.14	19.28		.04	4	24	28	.06		.04			
560.7	564.6	82007	3.9	3.7	2CE4	4.00	.08	3.65	10.34	30.79		.07	4	21	26	.06		.04			
564.6	567.7	82008	3.1	3.1	2L34	3.05	.13	2.15	3.72	30.79		.10	4	5	9	.20		.03			
567.7	570.8	82009	3.1	3.0	2L3	2.81	.07	.24	.22	9.02		.04	2	3	5	.14		.02			
570.8	575.0	82010	4.2	4.2	2B45	2.94	.11	1.18	4.29	21.77		.07	4	3	7	.19		.02			
575.0	579.2	82011	4.2	4.2	2B45	2.95	.10	1.93	4.93	51.01		1.30	3	2	5	.21		.01			
579.2	583.2	82012	4.0	4.0	2A0	2.88	.16	.67	2.35	16.17		.14	4	4	8	.17		.01			
583.2	587.2	82013	4.0	4.0	2A0	2.78	.14	.52	1.06	10.58		.04	3	3	7	.11		.01			
587.2	591.2	82014	4.0	3.9	2A0	1.79	.08	.65	.91	11.82		.04	2	2	5	.11		.01			
591.2	595.3	82015	4.1	3.7	2A4	2.92	.13	1.86	2.90	64.07		1.27	3	2	6	.15		.05			
600.8	604.8	82016	4.0	4.0	2B05	2.83	.05	.91	1.67	18.97		.07	2	1	4	.24		.03			
604.8	608.9	82017	4.1	4.1	2L14	2.79	.11	.70	1.19	19.91		.04	2	2	5	.13		.01			

DDH: 82F-03 UTM-N: 8218.2 UTM-E: 16073.9 UTM-ELEV: 4036.4 TOTAL DEPTH: 627.0 SECTION: 127+600E
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	Ba0 %	Hg %	Mn %	As %	Ba %	S.G. W.R.
394.8	398.3	82018	3.5	3.5	2GE4	4.43	.10	5.37	9.25	101.40		.10	3	19	22	9.96		.12			
423.4	428.3	82019	4.9	4.9	2H46	3.82	.20	2.32	2.40	51.32		.07	10	15	26	4.83		.14			
428.3	432.0	82020	3.7	3.7	2E48	4.72	.24	2.31	2.60	34.52		.10	8	28	36	.15		.29			
432.0	436.3	82021	4.3	4.1	2E8	4.67	.36	1.49	1.38	29.86		.04	5	30	36	.03		.17			
436.3	441.0	82022	4.7	4.7	2E0	4.53	.09	.88	.60	16.79			1	32	34	.08		.02			
441.0	449.7	82023	8.7	8.4	2E0	4.51	.08	.77	.42	12.75			1	33	34	.07		.02			
449.7	456.9	82024	7.2	7.2	2C3	3.73	.13	.35	.33	16.49				23	24	.03		.01			
456.9	464.5	82025	7.6	7.6	2C3	3.86	.05	.84	.50	18.35				25	26	.02		.01			
464.5	465.3	82026	.8	.8	2H19	3.75	.59	1.06	.23	15.55			30	8	38			.03			
465.3	470.5	82027	5.2	5.2	2CE0	3.92	.09	1.36	1.84	21.46		.14	2	24	26	.01		.02			
470.5	475.7	82028	5.2	5.2	2CE0	3.94	.05	1.15	1.00	29.55		.69		26	26	.01		.01			
475.7	480.8	82029	5.1	5.1	2CE0	3.32	.17	2.69	1.01	140.59		5.08		14	15	.01		.01			
480.8	485.9	82030	5.1	5.1	2CE0	3.92	.12	1.66	1.99	22.08		.07	1	24	26	.03		.04			
485.9	491.0	82031	5.1	5.1	2CE4	4.13	.08	2.55	4.65	22.08		.04	2	25	27	.05		.04			
491.0	497.2	82032	6.2	6.2	2A14	3.41	.03	2.35	4.68	30.17		.10	1	13	14	.24		.01			
497.2	501.8	82033	4.6	4.6	2CE4	4.26	.20	1.64	2.92	18.35		.04	5	25	31	.01		.17			
501.8	506.4	82034	4.6	4.6	2CE4	4.00	.37	1.74	2.83	18.97		.04	5	22	27	.01		.20			
506.4	511.0	82035	4.6	4.6	2CE8	3.91	.56	1.12	1.60	20.84		.04	5	21	26	.01		.14			
511.0	515.2	82036	4.2	4.2	2F10	4.55	.17	3.58	5.93	28.30		.04	7	24	31	.02		.29			
515.2	519.3	82037	4.1	4.1	2F14	4.19	.21	5.30	7.08	34.53		.04	5	20	26			.15			
519.3	523.4	82038	4.1	4.1	2F14	4.53	.20	6.30	10.03	40.44		.04	7	20	28	.01		.31			
523.4	528.6	82039	5.2	5.2	2CE0	4.33	.21	1.38	2.54	9.64		.04	6	25	32	.01		.18			
528.6	533.7	82040	5.1	5.1	2CE0	3.89	.33	.40	1.10	8.71		.14	4	23	27	.02		.11			
533.7	538.8	82041	5.1	5.1	2CE0	3.94	.39	.39	1.69	7.15		.04	4	23	27	.07		.10			
538.8	543.1	82042	4.3	4.3	2D34	4.15	.15	3.40	8.47	12.75		.04	3	21	25	.01		.05			
543.1	547.3	82043	4.2	4.2	2D34	4.48	.09	4.67	8.83	15.24		.04	2	25	27	.03		.02			
547.3	551.5	82044	4.2	4.2	2D34	4.24	.07	6.02	10.64	19.28		.04	3	21	24	.02		.02			
551.5	554.8	82045	3.3	3.3	2D34	4.15	.08	1.51	4.34	7.15		.04	2	24	27	.01		.03			
554.8	558.2	82046	3.4	3.4	2D34	4.07	.06	5.22	10.09	24.88		.04	2	18	21	.05		.03			
558.2	562.7	82047	4.5	4.5	2B05	2.87	.11	.82	1.44	22.08		.34	2	1	4	.31		.03			
562.7	567.2	82048	4.5	4.5	2B05	2.92	.12	1.79	1.57	26.44		.14	2	2	4	.24		.02			
567.2	571.7	82049	4.5	4.5	2B05	2.94	.15	.41	1.49	12.13		.14	3	3	7	.18		.01			
571.7	576.2	82050	4.5	4.5	2B05	2.92	.22	.44	1.37	19.60		.28	3	3	6	.17		.02			
576.2	580.5	82051	4.3	4.3	2D4	3.41	.29	3.23	10.10	39.19		.21	4	8	13	.09		.03			

DDH: 82F-05 UTM-N: 7889.3 UTM-E: 14894.5 UTM-ELEV: 3913.1 TOTAL DEPTH: 407.0 SECTION: 127
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
273.2	277.7	82052	4.5	4.5	2A4	3.25	.30	.62	3.83	14.61		.10	5	10	15	.04		.03			
277.7	282.2	82053	4.5	4.5	2A4	2.89	.06	5.18	9.88	30.17		.28	2	9	11	.05		.01			
282.2	287.2	82054	5.0	4.8	2E24	4.82	.08	3.14	3.52	36.08		.07	2	26	28	.02		.04			
287.2	291.4	82055	4.2	4.2	2E74	4.45	.20	6.32	8.47	130.33		.14	9	16	25	1.12		.24			
291.4	296.8	82056	5.4	5.4	2B4	3.12	.15	3.37	7.55	49.46		.07	4	4	8	.22		.15			
296.8	302.2	82057	5.4	4.7	2B4	2.86	.06	2.47	3.87	30.01		.07	2	2	5	.07		.05			
302.2	306.6	82058	4.4	4.4	2E4	4.45	.32	6.42	7.38	113.53		.17	12	14	26	.09		.32			
306.6	310.2	82059	3.6	3.6	2H4	4.40	.42	4.39	6.93	69.36		.07	38		39	.54		.14			
310.2	313.7	82060	3.5	3.0	2H4	4.39	.41	2.92	3.39	51.32		.10	40	2	42	.05		.06			
313.7	318.7	82061	5.0	4.9	2H4	4.40	.52	2.62	3.87	48.83		.10	43		43	.03		.05			
318.7	323.7	82062	5.0	5.0	2H4	4.44	.50	2.87	4.31	53.81		.10	43		44	.03		.06			
323.7	328.7	82063	5.0	5.0	2H4	4.23	.55	2.64	2.76	60.03		.14	40		40	.02		.06			
328.7	333.9	82064	5.2	5.2	2H4	4.41	.42	3.38	5.35	61.51		.14	42		42	.01		.08			
333.9	338.8	82065	4.9	4.9	2B57	3.03	.26	.52	1.76	21.77		.10	10	1	12	.25		.01			
338.8	344.0	82066	5.2	5.2	2B5	2.87	.13	.72	1.55	14.00		.07	5	2	8	.29		.01			
344.0	349.0	82067	5.0	5.0	2A0	2.69	.04	.36	.93	12.44		.07	4		4	.43		.05			
349.0	354.0	82068	5.0	5.0	2A0	2.69	.02	.59	1.50	6.53		.04	1	1	3	.54		.02			
354.0	359.0	82069	5.0	5.0	2A4	2.77	.08	1.38	2.94	25.82		.10	2	1	3	.71		.02			
359.0	363.9	82070	4.9	4.9	2A0	2.77	.03	.82	1.71	16.49		.17	2	2	4	.44		.01			

DDH: 82F-06 UTM-N: 8467.3 UTM-E: 14924.0 UTM-ELEV: 4069.0 TOTAL DEPTH: 792.0 SECTION: 124
 RFE: S2 RFE DIR: 200 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
462.2	464.6	82071	2.4	2.2	2DE	3.38	.21	1.38	4.34	16.17			.14	14	7	22	.55				.09
464.6	469.0	82072	4.4	4.4	2G0	4.63	.03	3.15	5.37	32.04			.14	1	16	17	29.87				.01
469.0	473.5	82073	4.5	4.5	2G4	4.59	.06	4.17	6.33	56.92			.10		10	11	42.93				.01
473.5	476.8	82074	3.3	3.3	2E4	4.51	.03	4.13	6.36	42.30			.10	1	28	29	2.26				.01
476.8	480.0	82075	3.2	3.0	2E4	4.60	.03	4.57	7.68	52.25			.07	1	25	27	2.99				.01
480.0	484.8	82076	4.8	4.8	2G0	3.48	.04	2.85	5.07	30.48			.10		14	15	37.90				.01
484.8	489.6	82077	4.8	4.8	2G4	4.51	.05	3.56	6.52	57.23			.10	2	16	18	26.42				.06
512.0	515.9	82078	3.9	3.9	2A0	2.73	.02	.39	.38	4.04				2	2	4	2.87				.02
515.9	519.8	82079	3.9	3.9	2A0	2.74	.02	.23	.30	5.91				2	2	4	2.80				.02
519.8	525.9	82080	6.1	6.1	2L0	3.04	.05	.81	1.00	12.75				4	4	8	2.87				.08
525.9	528.9	82081	3.0	3.0	2A0	2.78	.03	.45	.36	6.22				1	2	3	3.38				.03
528.9	533.0	82082	4.1	4.1	2L41	2.92	.06	1.19	1.94	17.42			.10	4	3	7	4.72				.10
533.0	537.1	82083	4.1	4.1	2E4	4.44	.13	4.75	6.40	75.58			.14	8	19	27	6.19				.11
537.1	541.2	82084	4.1	4.1	2E4	4.08	.23	4.63	6.52	71.54			.14	12	17	29	.16				.09
541.2	545.3	82085	4.1	4.1	2E4	4.33	.30	5.72	8.17	100.46			.14	21	11	33	.57				.07
545.3	548.8	82086	3.5	3.5	2D0	2.84	.06	1.62	2.50	41.99			.10	3	2	6	.12				.03
548.8	552.2	82087	3.4	3.4	2D07	2.87	.14	3.90	2.96	122.55			.17	8	7	15	.47				.07
552.2	555.7	82088	3.5	3.5	2E47	4.38	.15	4.33	5.02	95.49			.21	7	22	30	.38				.14
555.7	559.1	82089	3.4	3.4	2E07	4.15	.28	.63	.44	12.75				16	18	34	.01				.09
559.1	563.4	82090	4.3	4.3	2H0	4.36	.43	.75	.21	18.97				37	6	43	.01				.11
563.4	567.2	82091	3.8	3.8	2E0	4.71	.15	1.05	.74	21.46				7	28	35	.01				.19
567.2	569.5	82092	2.3	2.3	2E8	4.70	.11	1.09	1.07	25.19			.14	9	27	36	.03				.33
569.5	575.0	82093	5.5	5.5	2E4	4.48	.28	3.32	4.72	59.41			.10	9	24	33	.01				.27
575.0	580.5	82094	5.5	4.0	2E48	4.58	.20	2.06	2.74	37.95			.07	9	25	34	.01				.37
580.5	589.9	82095	9.4	5.7	2F0	4.48	.16	2.73	3.89	39.50			.07	1	30	32	.01				.01
589.9	604.0	82096	14.1	6.0	2F0	4.76	.06	3.22	6.03	36.08			.04	1	32	33	.02				.02
604.0	608.4	82097	4.4	3.4	2F4	4.70	.07	4.76	9.66	44.48			.07	2	29	31	.02				.02
608.4	612.8	82098	4.4	3.2	2F4	4.89	.03	4.07	7.88	41.06			.04	1	31	33	.35				.02
612.8	615.5	82099	2.7	2.2	2G0	4.85	.03	2.71	6.83	29.24			.04	1	25	27	11.08				.03
615.5	617.8	82100	2.3	2.0	2E41	4.23	.16	2.90	3.42	31.73			.04	3	26	30	.30				.13
617.8	622.0	82101	4.2	4.1	2F4	4.76	.10	5.43	10.60	65.32			.07	4	25	29	.03				.09
622.0	625.4	82102	3.4	3.4	2H43	4.31	.54	4.13	8.87	48.21			.04	29	8	37	.03				.17
625.4	629.4	82103	4.0	4.0	2F41	4.63	.17	4.26	9.11	36.08			.04	6	24	30	.04				.16
629.4	633.4	82104	4.0	4.0	2G41	4.53	.19	3.28	7.52	37.64			.07	4	21	26	9.37				.15
633.4	637.4	82105	4.0	4.0	2G0	4.49	.15	2.61	5.60	31.73			.07	3	23	26	7.03				.09
637.4	641.8	82106	4.4	4.4	2F4	4.46	.17	4.24	9.28	32.04			.07	4	24	28	1.20				.14
641.8	646.3	82107	4.5	4.5	2F4	4.89	.14	4.70	8.90	39.81			.04	2	26	29	3.45				.08
646.3	650.8	82108	4.5	4.5	2F0	4.66	.19	3.27	6.28	34.46			.04	6	26	33	.89				.25
650.8	655.3	82109	4.5	4.5	2F4	4.79	.22	5.69	8.30	51.32			.04	5	24	29	3.94				.21
655.3	660.3	82110	5.0	5.0	2F0	4.57	.17	2.77	6.19	21.46			.07	4	27	31	.06				.09
660.3	665.3	82111	5.0	5.0	2F0	3.99	.26	2.95	5.94	34.21			.07	13	18	31	.04				.09
665.3	670.3	82112	5.0	5.0	2F4	4.66	.06	3.19	6.71	22.08			.07	3	31	34	.01				.03
670.3	675.3	82113	5.0	5.0	2F4	4.71	.12	4.42	8.35	32.35			.07	5	26	31	.03				.02
675.3	679.2	82114	3.9	3.9	2D3	3.04	.07	2.13	4.15	27.05			.14	4	6	11	.53				.06
679.2	683.1	82115	3.9	3.9	2D3	3.12	.05	1.71	4.74	21.46			.10	4	8	12	.16				.03
683.1	687.0	82116	3.9	3.9	2D34	3.37	.03	2.11	8.26	33.90			.28	3	13	16	.16				.02
687.0	690.8	82117	3.8	3.8	2D5	3.04	.05	1.57	5.37	24.88			.17	3	3	6	.28				.01
690.8	694.7	82118	3.9	3.9	2D5	2.97	.06	2.19	5.73	30.48			.07	4	5	9	.18				.01
694.7	697.0	82119	2.3	2.3	2A4	3.09	.03	2.75	6.70	35.15			.28	3	3	6	.30				.02
697.0	702.3	82120	5.3	5.3	2D3	3.31	.06	2.69	6.03	35.77			.17	4	11	16	.16				.01

DDH: 82F-06 UTM-N: 8467.3 UTM-E: 14924.0 UTM-ELEV: 4069.0 TOTAL DEPTH: 792.0 SECTION: 124
 RFE: S2 RFE DIR: 200 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
702.3	707.6	82121	5.3	5.3	2D3	3.21	.20	2.75	4.99	50.70		.28	6	7	13	.21		.03			
707.6	712.9	82122	5.3	5.3	2D3	3.22	.09	2.95	5.57	37.64		.10	4	8	12	.17		.01			
712.9	718.3	82123	5.4	5.4	2D43	3.40	.05	3.63	6.84	40.12		.17	4	11	15	.12		.03			
718.3	723.7	82124	5.4	5.4	2D3	3.42	.04	2.01	6.85	27.99		.14	4	11	16	.12		.02			
723.7	729.1	82125	5.4	5.4	2D3	3.26	.06	2.55	5.81	35.46		.21	5	9	14	.16		.01			
729.1	734.5	82126	5.4	5.4	2D43	3.39	.08	3.90	6.90	46.35		.17	6	7	14	.09		.01			
734.5	739.2	82127	4.7	4.7	2C35	3.33	.13	1.31	3.19	17.11		.10	10	8	18	.07		.02			
739.2	743.9	82128	4.7	4.7	2C35	3.50	.08	2.51	4.32	36.08		.14	4	14	19	.06		.01			
743.9	748.6	82129	4.7	4.7	2C35	3.21	.11	1.56	2.90	29.55		.10	8	6	15	.11		.01			
748.6	753.3	82130	4.7	4.7	2C35	3.13	.11	1.19	3.75	28.93		.07	5	7	13	.07		.01			
753.3	756.4	82131	3.1	3.1	2A41	2.89	.06	1.91	4.99	33.28		.62	2	2	5	.11		.01			
756.4	759.4	82132	3.0	3.0	2A41	2.86	.06	1.70	2.86	33.90		.21	4	2	6	.17		.04			

DDH: 82F-07 UTM-N: 7890.6 UTM-E: 14693.4 UTM-ELEV: 3912.8 TOTAL DEPTH: 422.0 SECTION: 126
 RFE: S2 RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
337.1	340.5	82133	3.4	3.4	2A0	3.26	.27	.06	.08	13.47			3	13	17	.11		.05			
340.5	343.9	82134	3.4	3.4	2C5	3.55	.34	.34	.91	22.40			2	21	23	.03		.03			
343.9	348.9	82135	5.0	4.5	2A41	3.24	.19	1.53	5.71	33.28		.21	4	10	15	.03		.06			
348.9	352.1	82136	3.2	2.6	2F0	3.19	.12	1.84	5.99	25.19		.41	3	9	12	.08		.05			
352.1	355.3	82137	3.2	3.2	2A0	3.06	.12	1.02	2.34	37.01		.72	1	9	10	.17		.02			
355.3	359.6	82138	4.3	4.3	2F4	4.81	.17	6.21	6.72	84.91		.14	5	27	32	.54		.28			
359.6	363.9	82139	4.3	4.3	2F4	4.55	.13	4.83	5.98	83.36		.14	7	17	25	6.17		.27			
363.9	368.4	82140	4.5	4.5	2B4	2.96	.16	2.88	3.50	42.61		.10	3	3	7	1.15		.01			
368.4	372.6	82141	4.2	4.0	2A4	3.04	.07	1.59	4.97	29.55		.07	4	5	10	.20		.01			
372.6	376.9	82142	4.3	4.3	2A0	2.89	.03	1.10	2.15	22.08		.07	4	3	7	.47		.01			
376.9	381.2	82143	4.3	4.3	2A0	2.82	.04	.96	2.62	18.66		.10	3	2	6	.40		.03			
381.2	385.5	82144	4.3	4.3	2A4	2.95	.08	1.88	2.93	34.84		.10	5	4	9	.23		.04			

DDH: 82F-08 UTM-N: 8091.1 UTM-E: 14697.7 UTM-ELEV: 3908.9 TOTAL DEPTH: 541.0 SECTION: 125
 RFE: S2 RFE DIR: 200 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
361.9	366.1	82145	4.2	4.2	2CE0	3.32	.24	.08	.07	17.11			1	17	18	.01					.02
366.1	369.6	82146	3.5	3.5	2C3	3.77	.18	.03	.03	10.89			5	21	26	.02					.05
369.6	373.0	82147	3.4	3.4	2C3	3.62	.41	.42	.26	15.86			11	14	26	.02					.08
373.0	378.1	82148	5.1	5.1	2E4	4.12	.23	4.57	6.58	76.20			7	18	26	2.55					.31
378.1	383.4	82149	5.3	5.3	2C56	2.77	.02	.68	.57	6.53			2	2	4	4.04					.06
383.4	388.9	82150	5.5	5.5	2L14	3.00	.02	2.00	2.57	36.08			4	3	7	3.16					.08
388.9	393.9	82151	5.0	4.9	2A0	2.81	.01	.60	.69	8.40			3	2	5	3.13					.03
393.9	398.9	82152	5.0	4.5	2A0	2.89	.01	.55	.73	8.40			2	1	4	3.01					.04
398.9	402.4	82153	3.5	3.5	2L0	3.08	.06	.95	.64	16.49			4	5	9	2.55					.04
402.4	406.0	82154	3.6	3.4	2L0	3.01	.03	.48	.67	7.15			2	2	5	3.36					.03
406.0	410.1	82155	4.1	4.0	2L14	3.14	.07	1.83	2.18	31.42		.07	4	4	9	7.92					.09
410.1	414.2	82156	4.1	4.1	2L14	3.16	.06	2.88	2.42	62.52		.07	6	4	11	4.51					.13
414.2	419.7	82157	5.5	5.5	2H4	3.73	.15	6.67	6.10	135.92		.07	21	2	24	.12					.16
419.7	425.2	82158	5.5	5.5	2H4	3.94	.25	4.39	7.73	90.20		.07	22	7	29	.19					.14
425.2	430.7	82159	5.5	5.4	2H4	4.48	.31	6.86	7.15	148.05		.07	24	8	32	3.61					.24
430.7	436.3	82160	5.6	5.6	2E42	4.80	.11	2.97	3.82	33.59		.07	7	29	36	.05					.08
436.3	441.9	82161	5.6	5.4	2E42	4.70	.20	2.75	4.16	39.50		.07	12	26	39	.07					.07
441.9	445.6	82162	3.7	3.7	2D5	3.07	.20	3.05	6.08	72.16		.10	5	6	11	.18					.06
445.6	449.7	82163	4.1	4.1	2D5	3.16	.20	1.07	3.22	29.86		.07	8	3	11	.23					.05
449.7	451.9	82164	2.2	2.2	2H4	4.36	.51	2.78	4.41	40.44		.07	42	2	44	.02					.12
451.9	457.6	82165	5.7	5.7	2E2	4.63	.65	1.12	1.82	20.53		.10	12	25	38	.03					.17
457.6	463.2	82166	5.6	5.6	2E2	4.18	.27	.83	3.60	10.26		.07	5	27	33	.03					.14
463.2	468.8	82167	5.6	5.6	2E2	4.80	.14	3.00	4.82	18.04		.07	2	31	34	.02					.06
468.8	472.4	82168	3.6	3.6	2D4	3.33	.13	.52	3.50	9.64		.14	3	14	17	.16					.03
472.4	474.2	82169	1.8	1.8	2E0	4.44	.21	.18	2.21	7.78		.07	3	31	35	.04					.04
474.2	476.4	82170	2.2	2.2	2L0	3.04	.19	.96	.48	14.00		.07	5	9	14	.15					.01
476.4	480.0	82171	3.6	3.6	2E4	4.34	.22	4.97	8.00	99.22		.14	9	22	31	.02					.09
496.0	498.5	82172	2.5	2.4	2A1	2.93	.11	.13	.31	10.58			4	3	8	.11					.03
498.5	502.0	82173	3.5	3.5	2L0	2.86	.04	.03	.06	6.53			2	1	3	.19					.01
502.0	505.6	82174	3.6	3.6	2C5	2.88	.15	.34	.37	51.01			5	5	10	.15					.03
505.6	509.3	82175	3.7	3.7	2C5	3.08	.18	.14	.11	13.38			7	7	14	.10					.05
509.3	514.4	82176	5.1	5.1	2A0	2.93	.13	.33	.16	9.64			5	2	8	.18					.01
514.4	519.5	82177	5.1	5.1	2A0	2.97	.13	1.39	.48	27.99			5	3	9	.16					.01
519.5	524.8	82178	5.3	5.1	2A41	2.75	.03	1.54	3.10	13.69			1		1	.19					.01
524.8	530.0	82179	5.2	4.0	2A1	2.87	.07	1.16	2.40	26.13			2	1	4	.20					.03

DDH: 82F-09 UTM-N: 8296.2 UTM-E: 14692.8 UTM-ELEV: 4040.1 TOTAL DEPTH: 667.0 SECTION: 124
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
491.2	495.8	82180	4.6	4.6	2E4	3.70	.18	2.74	4.79	42.61		.10	6	12	19	2.79		.12			
495.8	500.3	82181	4.5	4.5	2E4	4.41	.12	4.83	4.26	79.00		.17	7	16	23	4.38		.39			
500.3	504.8	82182	4.5	4.5	2E4	4.29	.21	6.63	5.58	107.93		.10	8	12	20	8.48		.45			
504.8	509.5	82183	4.7	4.7	2A0	2.83	.01	.25	.30	5.91			2	1	4	2.45		.07			
509.5	514.3	82184	4.8	4.8	2A0	2.79	.02	.40	.52	6.53			2	2	4	2.52		.06			
514.3	519.1	82185	4.8	4.8	2A0	2.79	.03	.51	.80	7.78			2	2	4	1.35		.06			
519.1	523.9	82186	4.8	4.8	2A0	2.68	.02	.25	.30	.93			2	1	3	2.34		.02			
530.4	533.4	82187	3.0	3.0	2D4	3.47	.13	6.35	7.05	137.79		.07	8	5	14	.73		.21			
536.5	540.6	82188	4.1	4.1	2B0	2.87	.04	.86	1.61	10.26		.04	3	2	5	.26		.05			
540.6	544.7	82189	4.1	4.1	2B0	3.03	.06	1.20	2.35	21.46		.04	3	4	8	.08		.06			
547.7	552.2	82190	4.5	4.0	2B4	3.19	.14	8.38	1.95	144.01		.14	5	5	10	.05		.10			
552.2	556.6	82191	4.4	4.2	2B4	3.27	.10	7.90	3.39	162.67		.10	4	6	11	.07		.10			
556.6	561.5	82192	4.9	4.9	2B4	3.09	.08	3.67	1.96	69.05		.04	4	3	8	.07		.06			
561.5	566.4	82193	4.9	4.9	2B0	3.08	.09	.76	1.72	17.11		.04	7	4	11	.46		.09			
566.4	571.2	82194	4.8	4.8	2C0	3.21	.24	.84	1.95	13.37		.07	8	8	16	.18		.07			
571.2	574.2	82195	3.0	3.0	2E42	4.72	.15	3.30	5.63	35.46		.04	4	28	32	.02		.09			
574.2	577.3	82196	3.1	3.1	2E42	4.81	.13	3.57	6.51	36.39		.04	3	29	33	.02		.06			
577.3	581.7	82197	4.4	4.4	2H4	4.51	.45	2.29	4.15	29.24		.04	24	14	38	.03		.14			
581.7	586.1	82198	4.4	4.4	2H4	4.51	.48	3.79	6.46	31.10		.04	29	8	37	.03		.09			
586.1	590.5	82199	4.4	4.4	2H4	4.51	.62	2.66	5.06	35.15		.04	24	14	38	.02		.16			
590.5	596.0	82200	5.5	5.5	2E2	4.18	.27	1.94	3.58	14.31		.04	7	23	31	.05		.17			
596.0	600.5	82201	4.5	4.5	2A0	3.20	.16	1.06	2.06	22.71		.04	10	4	15	.14		.15			
600.5	604.9	82202	4.4	4.4	2A0	3.14	.11	.94	2.10	22.71		.04	6	7	13	.18		.08			
604.9	609.3	82203	4.4	4.4	2A4	3.08	.10	1.48	2.53	40.12		.04	5	6	12	.16		.05			
609.3	612.6	82204	3.3	3.3	2C0	3.00	.08	.62	2.62	19.91		.04	5	4	10	.21		.05			
612.6	615.9	82205	3.3	3.3	2D0	3.13	.14	3.17	4.87	93.62		.04	5	6	12	.20		.03			
615.9	619.2	82206	3.3	3.3	2A0	2.83	.05	1.11	2.82	25.82		.04	3	1	4	.20		.06			
619.2	624.8	82207	5.6	5.6	2C0	2.99	.08	.19	.22	5.91			3	4	7	.22		.04			
624.8	630.3	82208	5.5	5.5	2L12	2.84	.04	.42	.69	9.02			2	1	4	.27		.04			
630.3	635.8	82209	5.5	5.4	2D0	3.25	.19	3.48	4.14	81.49			7	8	15	.09		.10			
635.8	641.3	82210	5.5	5.5	2L12	2.90	.08	.58	.12	18.35			4	3	8	.22		.06			

DDH: 82F-10 UTM-N: 7792.2 UTM-E: 14389.4 UTM-ELEV: 3940.6 TOTAL DEPTH: 627.0 SECTION: 125
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
517.2	519.7	82211	2.5	2.5	0Q9	2.96	.12	.70	2.54	18.97				6	4	11	.19				.08
519.7	521.5	82212	1.8	1.8	2L0	2.84	.09	.12	.09	3.73				3	3	6	.26				.04
521.5	526.0	82213	4.5	4.5	2A0	2.77	.07	.40	.57	9.64				2	2	5	.32				.04
526.0	530.5	82214	4.5	4.3	2A0	2.83	.10	1.33	3.59	23.33		.07	3	2	6	.18				.03	
530.5	533.4	82215	2.9	2.9	2E46	4.03	.19	4.82	6.77	79.63		.14	8	14	22	1.41				.04	
533.4	536.6	82216	3.2	3.2	2E46	4.26	.07	4.97	9.14	65.32		.04	3	19	22	2.23				.08	
536.6	539.8	82217	3.2	3.2	2E4	4.24	.13	5.50	9.77	78.07		.04	3	19	22	.29				.09	
539.8	541.9	82218	2.1	2.1	2D06	2.99	.16	4.51	5.41	89.58		.04	3	3	6	1.12				.06	
541.9	543.7	82219	1.8	1.8	2H4	4.08	.36	5.85	8.51	110.11		.07	26	5	32	.96				.08	
543.7	548.8	82220	5.1	5.1	2A0	2.89	.06	.97	1.75	21.77		.04	4	3	7	.24				.04	
548.8	553.9	82221	5.1	5.1	2A0	2.89	.10	.51	1.17	22.39			3	3	7	.20				.01	
553.9	556.9	82222	3.0	3.0	2A0	2.80	.01	.70	1.35	23.33			2	1	3	.23				.01	
566.4	570.2	82223	3.8	3.8	2A1	2.76	.03	.57	.98	15.86			3	3	6	.23				.04	
570.2	574.1	82224	3.9	3.9	2A1	2.87	.05	.88	1.83	16.49			3	3	6	.18				.03	

DDH: 82F-11 UTM-N: 8094.9 UTM-E: 14491.6 UTM-ELEV: 4009.4 TOTAL DEPTH: 603.6 SECTION: 124
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
496.6	500.8	82225	4.2	4.2	2A4	3.00	.10	1.39	4.28	13.38		.07	4	7	12	.07		.05			
500.8	505.0	82226	4.2	4.2	2A4	3.19	.08	3.11	7.43	25.51		.55	2	5	7	.10		.01			
505.0	510.0	82227	5.0	5.0	2E4	4.44	.20	5.70	5.85	79.32		.14	4	21	26	4.25		.15			
510.0	515.0	82228	5.0	5.0	2E4	4.74	.11	5.74	6.61	96.11		.14	5	18	23	8.59		.21			
515.0	519.5	82229	4.5	4.5	2H4	4.12	.35	4.89	5.87	90.20		.07	16	12	28	4.56		.25			
519.5	524.0	82230	4.5	4.5	2H0	4.53	.49	2.96	5.00	46.66		.04	33	5	38	.07		.11			
524.0	528.0	82231	4.0	4.0	2D0	3.03	.13	2.70	4.35	50.08		.04	6	5	12	.13		.09			
528.0	532.1	82232	4.1	4.1	2D0	2.95	.08	1.24	2.97	25.19		.04	3	3	7	.19		.05			
532.1	536.2	82233	4.1	4.1	2D0	3.02	.12	1.93	3.53	33.90		.04	4	4	9	.14		.05			
536.2	539.6	82234	3.4	3.4	2A4	2.79	.12	1.20	3.25	24.88		.04	4	2	7	.34		.05			
539.6	543.0	82235	3.4	3.4	2A0	2.82	.09	1.17	2.32	23.33		.04	3	2	5	.44		.02			
543.0	547.0	82236	4.0	4.0	2B45	2.80	.08	1.20	2.61	21.46		.04	4	3	7	.34		.04			
547.0	550.9	82237	3.9	3.9	2B45	3.00	.15	1.52	3.33	47.90		.04	5	3	8	.32		.03			
550.9	555.8	82238	4.9	4.4	2A0	2.78	.05	.96	1.76	19.28		.04	2	3	5	.26		.03			
555.8	560.7	82239	4.9	4.0	2A0	2.74	.05	1.37	1.50	31.42		.07	2	2	5	.44		.03			
560.7	565.6	82240	4.9	4.9	2A0	2.84	.06	1.12	1.39	25.19		.14	2	2	5	.36		.03			
565.6	570.5	82241	4.9	4.8	2A0	2.73	.03	1.09	2.48	15.24		.14	2		3	.36		.02			
570.5	575.5	82242	5.0	3.7	2A4	2.79	.03	1.22	3.27	15.24		.14	2		3	.50		.03			

DDH: 82F-12 UTM-N: 7283.0 UTM-E: 14897.5 UTM-ELEV: 3875.4 TOTAL DEPTH: 451.0 SECTION: 130
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
6 335.2	340.0	82243	4.8	4.6	2E4	3.28	.12	4.22	8.01	52.88		.10	4	9	13	.07		.11			
340.0	344.4	82244	4.4	4.4	2DA0	2.88	.06	3.35	4.38	46.66		.04	2	2	5	.11		.07			
5 344.4	348.7	82245	4.3	4.3	2DA0	2.96	.05	2.07	2.95	30.79		.04	4	2	6	.40		.05			
348.7	353.0	82246	4.3	4.3	2DA0	2.92	.05	1.91	3.30	26.13		.04	3	2	6	.29		.06			
0 353.0	357.3	82247	4.3	4.3	2CA0	2.82	.06	.94	2.13	16.80		.04	5	2	7	.55		.07			
6 357.3	361.9	82248	4.6	4.2	2H0	4.02	.32	2.39	4.42	42.92		.04	26	6	32	.32		.08			
4 361.9	366.9	82249	5.0	5.0	2D5	2.97	.13	1.54	2.85	29.55		.04	5	4	9	.44		.04			

DDH: 82F-13 UTM-N: 7870.9 UTM-E: 14270.2 UTM-ELEV: 3946.6 TOTAL DEPTH: 641.0 SECTION: 124
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
559.5	565.3	82250	5.8	5.8	2A01	2.83	.08	.66	2.28	17.73		.07	4	2	7	.17		.04			
565.3	571.0	82251	5.7	5.4	2A01	2.78	.02	.87	2.25	17.73		.04	3	1	4	.32		.03			
571.0	575.6	82252	4.6	4.3	2B4	2.93	.03	1.95	3.62	36.08		.04	4	3	7	.23		.03			
575.6	580.1	82253	4.5	4.3	2B0	2.76	.02	.97	2.01	19.60		.04	2	1	3	.14		.01			
580.1	584.6	82254	4.5	4.1	2B0	2.79	.04	.66	2.50	17.11		.04	3	1	4	.16		.01			
584.6	588.0	82255	3.4	3.4	2D47	3.40	.21	4.16	8.31	89.89		.04	11	4	15	.20		.05			
588.0	591.4	82256	3.4	3.2	2D07	2.96	.38	2.18	4.10	49.77		.04	4	5	9	.19		.02			

DDH: 82F-14 UTM-N: 7517.5 UTM-E: 14524.1 UTM-ELEV: 3992.1 TOTAL DEPTH: 700.0 SECTION: 127
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
550.8	555.7	82257	4.9	4.9	2A1	2.98	.12	.32	.65	7.47				3	7	11	.12		.03		
555.7	560.6	82258	4.9	4.9	2A0	3.15	.07	1.28	2.02	12.44			.21	2	9	12	.08		.01		
560.6	565.5	82259	4.9	4.9	2A41	2.95	.06	1.27	3.46	14.93			.82	2	7	9	.17		.03		
565.5	569.4	82260	3.9	3.9	2F4&	4.35	.09	5.40	9.53	61.90			.04	5	21	26	.08		.12		
569.4	573.2	82261	3.8	3.8	2F4&	4.64	.11	5.15	6.06	78.38			.10	6	25	31	1.21		.21		
573.2	578.1	82262	4.9	4.9	2F46	4.37	.16	4.52	6.50	71.54			.14	7	21	28	3.62		.27		
578.1	583.0	82263	4.9	4.9	2F46	4.49	.18	4.78	5.53	77.76			.17	8	20	29	4.82		.30		
583.0	587.6	82264	4.6	4.6	2H42	4.27	.36	6.46	8.28	104.82			.10	22	10	32	.69		.21		
587.6	592.0	82265	4.4	4.4	2E4&	4.26	.21	4.89	7.18	76.83			.07	8	18	27	3.07		.21		
592.0	596.3	82266	4.3	4.3	2E4&	4.31	.54	5.57	9.33	74.34			.04	5	19	25	2.06		.11		
596.3	600.3	82267	4.0	4.0	2A4	2.95	.10	1.90	3.08	29.86			.04	5	3	9	.25		.07		
608.5	614.0	82268	5.5	5.5	2B5	2.91	.07	.96	2.34	18.35			.04	4	1	6	.18		.03		
618.7	624.4	82269	5.7	5.7	2A0	2.90	.05	.65	1.06	14.31			.04	3	2	6	.17		.17		
624.4	630.1	82270	5.7	5.3	2A0	2.88	.07	1.47	1.41	36.08			.04	3	2	6	.30		.41		
630.1	635.7	82271	5.6	5.6	2A4	2.94	.09	3.78	3.02	83.05			.14	3	2	5	.26		.06		
635.7	641.3	82272	5.6	5.6	2A4	3.03	.14	1.78	4.30	40.44			.41	7	3	10	.34		.04		
641.3	646.9	82273	5.6	5.6	2A0	2.14	.06	1.18	.83	24.88			.04	4	1	5	.57		.18		

DDH: 82F-15 UTM-N: 7087.1 UTM-E: 14693.1 UTM-ELEV: 4025.6 TOTAL DEPTH: 740.0 SECTION: 130
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
590.3	595.5	82274	5.2	5.0	2LHA*	3.39	.51	.45	.52	23.02			10	11	21	.11		.03			
595.5	598.4	82275	2.9	2.8	2D0	3.28	.13	2.39	7.46	26.44		.41	2	11	13	.07		.05			
598.4	601.2	82276	2.8	2.8	2A1	2.28	.09	2.03	5.78	28.93		.07	1	7	8	.16		.01			
601.2	605.2	82277	4.0	3.8	2E4	4.81	.16	4.34	4.86	60.65		.17	5	27	32	.96		.19			
605.2	609.3	82278	4.1	4.1	2E4	3.16	.11	4.08	5.27	64.99		.10	5	26	31	3.99		.14			
609.3	610.2	82279	.9	.9	2H2	4.22	.54	4.99	6.26	97.04		.17	19	10	29	4.65		.35			
610.2	615.4	82280	5.2	5.2	2A4	2.22	.09	2.18	4.85	31.42		.07	6	1	7	.47		.05			
615.4	620.6	82281	5.2	5.2	2A4	3.00	.12	1.85	3.62	32.04		.04	4	3	8	.30		.03			
620.6	625.7	82282	5.1	4.7	2A0	2.93	.11	.94	1.78	27.99		.07	4	4	8	.55		.03			
625.7	630.8	82283	5.1	5.1	2A4	2.28	.09	1.46	4.29	31.42		.04	6	3	9	.26		.04			
630.8	635.9	82284	5.1	4.8	2A0	2.86	.07	.91	1.84	19.91		.07	4	2	7	.32		.02			
635.9	641.0	82285	5.1	5.1	2A0	2.23	.07	.98	2.53	24.26		.04	6	1	7	.35		.03			
641.0	646.1	82286	5.1	5.1	2A4	2.99	.09	1.70	4.22	32.66		.07	9	1	11	.37		.04			
646.1	651.2	82287	5.1	5.1	2A0	2.15	.08	.50	.93	15.24		.04	3	2	6	.49		.05			
672.0	676.5	82288	4.5	4.5	2A1	2.25	.07	.88	1.86	14.00		.04	5	4	9	.24		.06			
676.5	681.0	82289	4.5	4.1	2A41	2.62	.18	2.71	6.50	53.50		.07	10	13	23	.12		.03			

DDH: 82F-16 UTM-N: 7390.8 UTM-E: 14399.0 UTM-ELEV: 4004.4 TOTAL DEPTH: 707.0 SECTION: 127
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
631.0	635.1	82290	4.1	4.1	2A0	2.17	.08	.47	.65	9.64				4	3	8	.17		.08		
635.1	639.2	82291	4.1	3.6	2A0	2.73	.05	.15	.19	7.15				2	3	5	.51		.17		
639.2	643.3	82292	4.1	4.1	2A4	2.79	.06	1.44	2.70	37.32		.41	2	3	5	.19		.03			
643.3	645.5	82293	2.2	2.2	2G4	4.15	.05	3.35	7.37	48.43		.17	2	12	15	20.77		.09			
645.5	649.6	82294	4.1	4.1	2E4	4.06	.29	5.68	8.11	89.58		.07	12	17	29	.68		.20			
649.6	653.7	82295	4.1	4.1	2E4	4.32	.15	5.82	8.36	87.40		.04	6	20	27	.20		.23			
653.7	657.8	82296	4.1	4.1	2E4	4.36	.20	7.36	7.38	111.35		.07	7	21	29	.30		.18			
657.8	662.0	82297	4.2	4.2	2A4	2.77	.06	1.50	3.21	27.68		.34	2	4	6	.15		.01			
662.0	666.3	82298	4.3	4.3	2A0	2.77	.02	.63	1.62	12.44		.14	1	2	4	.14		.01			
666.3	670.6	82299	4.3	4.3	2A0	2.81	.05	1.26	2.54	30.79		.21	3	3	7	.45		.01			
670.6	676.4	82300	5.8	5.7	2A47	3.80	.36	3.15	6.34	79.00		.04	30		30	.06		.04			
676.4	682.0	82301	5.6	5.6	2A0	2.74	.05	.60	1.23	16.17			3	2	5	.15		.03			

DDH: 82F-17 UTM-N: 7695.4 UTM-E: 14898.2 UTM-ELEV: 3912.9 TOTAL DEPTH: 400.0 SECTION: 128
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
298.8	301.0	82302	2.2	2.2	2A0	2.81	.15	.03	.10	7.47				3	2	6	.53				.04
301.0	305.5	82303	4.5	4.5	2D5	3.33	.20	2.03	6.69	23.64		.21	6	12	18	.05				.09	
305.5	310.0	82304	4.5	4.5	2D5	3.37	.08	5.03	10.16	38.26		.21	4	8	13	.09				.05	
310.0	315.6	82305	5.6	5.6	2E42	4.44	.16	5.09	4.61	71.54		.07	9	19	29	.06				.24	
315.6	321.2	82306	5.6	4.4	2E42	4.48	.31	5.05	5.24	97.36		.04	16	13	29	.10				.39	
321.2	326.8	82307	5.6	5.6	2E42	4.45	.18	2.65	3.88	40.44		.04	9	20	29	.03				.15	
326.8	331.0	82308	4.2	4.2	2A41	2.98	.17	1.28	4.54	22.71		.07	5	3	8	.18				.05	
331.0	335.1	82309	4.1	4.1	2A1	2.79	.12	.93	1.93	18.04		.01	3	2	5	.45				.02	
335.1	339.2	82310	4.1	3.8	2A1	2.61	.03	.29	1.29	7.15			1		2	.68				.01	
339.2	344.2	82311	5.0	5.0	2A0	2.80	.06	.08	.32	4.98			3	3	7	.53				.03	
344.2	349.2	82312	5.0	5.0	2A0	2.79	.14	.08	.89	9.02			6		7	.30				.07	
349.2	354.2	82313	5.0	5.0	2A0	2.85	.13	1.42	.99	31.10			5	2	8	.32				.05	

DDH: 82F-22 UTM-N: 5158.4 UTM-E: 14959.7 UTM-ELEV: 4022.5 TOTAL DEPTH: 377.0 SECTION:
 RFE: RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS----						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
324.8	328.8	82314	4.0	3.5	2C5	2.91	.08	.16	.85	14.93			7	1	8	.75		.04			
328.8	330.5	82315	1.7	1.7	2E41	3.41	.16	2.44	6.42	42.61			8	9	17	.14		.04			
330.5	333.2	82316	2.7	2.7	2C0	3.10	.13	1.49	6.07	34.84			6	2	9	.20		.03			
333.2	335.5	82317	2.3	2.3	2E0	3.47	.16	1.85	5.04	39.81			7	10	17	.57		.02			
335.5	340.5	82318	5.0	4.0	2A0	2.75	.09	.16	.55	16.17			3	2	5	.26		.01			
342.2	343.4	82319	1.2	1.2	2E41	3.68	.21	1.40	7.20	96.42			11	12	23	.21		.03			
343.4	347.2	82320	3.8	2.8	2D0	3.19	.09	1.31	6.56	38.59			6	5	11	.27		.02			
347.2	351.2	82321	4.0	2.8	2C0	2.19	.12	.22	.45	13.69			2		3	.14		.02			

DDH: 82F-24 UTM-N: 6646.4 UTM-E: 15322.0 UTM-ELEV: 4007.4 TOTAL DEPTH: 127.0 SECTION: 135
 RFE: S2 RFE DIR: 0 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
32.0	35.5	82322	3.5	2.0	2E46	5.00	1.05	5.99	.82	102.02		.69		26	26	5.10		.02			
35.5	39.0	82323	3.5	1.8	2E46	4.54	.35	7.63	4.02	131.57		.55	1	20	21	6.73		.12			
39.0	45.0	82324	6.0	.8	2D06	3.08	.68	2.69	3.91	54.12		.17	1	5	6	3.87		.08			
45.0	48.0	82325	3.0	.2	2G0	3.20	.20	.28	4.57	15.24		.04	1	3	4	23.71		.10			
48.0	54.0	82326	6.0	2.3	2C0	2.87	.35	3.32	4.25	35.77		.07	1		2	2.43		.04			
54.0	60.0	82327	6.0	5.1	2A4	4.10	.14	4.41	5.23	55.99		.21	1	1	3	1.44		.02			
60.0	65.0	82328	5.0	5.0	2A4	2.86	.12	1.81	3.04	30.79		.07		3	4	.34		.01			
65.0	70.0	82329	5.0	5.0	2A4	2.92	.13	1.76	3.50	27.68		.07	1	3	4	2.83		.03			
70.0	75.5	82330	5.5	5.0	2A4	2.78	.10	3.53	1.22	53.19		.21		1	2	.60		.01			
82.0	87.0	82331	5.0	3.8	2A0	2.65	.08	.71	1.33	25.19		.07	8	1	9	.81		.04			
87.0	90.0	82332	3.0	3.0	2A0	2.67	.08	.66	.99	18.04			1	2	3	.52		.01			
90.0	94.5	82333	4.5	4.5	2A0	2.17	.03	.66	1.16	16.17			1	2	3	.49		.04			

DDH: 83F-01 UTM-N: 6783.0 UTM-E: 14782.1 UTM-ELEV: 4035.5 TOTAL DEPTH: 656.5 SECTION: 132+00E
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
568.0	569.2	82350	1.2	1.0	2E4	3.02	.12	2.43	4.27	30.17		.14	5	6	11	.20		.10			
569.2	575.0	82351	5.8	5.8	2A0	2.68	.03	.69	1.70	14.00		.13	1		1	.36		.02			
575.0	580.1	82352	5.1	5.1	2A0	2.74	.06	.79	1.15	22.08		.29	2	1	3	.29		.07			
580.1	584.3	82353	4.2	3.4	2A4	2.70	.05	3.14	3.56	65.94		.41	2	1	3	.28		.05			
584.3	586.9	82354	2.6	2.5	2L0	2.74	.07	.16	.26	6.53		.02	3	3	7	.94		.14			

DDH: 83F-02 UTM-N: 6577.2 UTM-E: 14564.5 UTM-ELEV: 4023.0 TOTAL DEPTH: 893.0 SECTION: 132+00E
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
0 721.6	723.7	82355	2.1	2.1	2A3	3.10	.20	.35	1.70	11.20		.33	7	8	16	.20		.04			
6 723.7	726.3	82356	2.6	2.6	2A4	3.00	.14	2.18	4.50	38.88		.21	4	5	10	.19		.02			
0 726.3	728.3	82357	2.0	2.0	2A0	2.80	.05	1.26	1.85	42.30		.90	1		2	.68		.02			
728.3	730.4	82358	2.1	2.1	2H46	4.20	.21	5.32	8.12	88.33		.16	17	10	28	5.98		.14			
730.4	737.0	82359	6.6	6.6	2E64	4.10	.10	4.29	6.78	61.90		.09	5	17	22	4.94		.10			
737.0	738.4	82360	1.4	1.4	2Q48	3.52	.38	4.88	3.11	87.40		.22	6	10	17	3.33		.11			
738.4	739.9	82361	1.5	1.3	2E46	4.46	.08	5.83	6.64	92.69		.11	4	22	26	5.85		.22			
739.9	743.0	82362	3.1	3.1	2D6	3.29	.10	2.92	4.72	42.61		.12	3	9	12	5.25		.06			
743.0	745.7	82363	2.7	2.6	2D64	3.52	.19	6.09	4.54	111.04		.38	4	11	15	12.05		.09			
6 745.7	749.9	82364	4.2	4.2	2G4	4.51	.22	4.64	5.80	67.81		.12	5	19	24	12.15		.22			
749.9	751.6	82365	1.7	1.7	2D36	4.15	.24	3.25	4.27	56.92		.17	5	16	22	15.74		.28			
751.6	755.6	82366	4.0	4.0	2G4	4.58	.22	4.72	4.99	84.91		.21	6	21	27	6.36		.27			
755.6	759.3	82367	3.7	3.4	2G4	4.67	.17	5.56	6.31	94.87		.18	6	19	26	8.98		.26			
759.3	762.6	82368	3.3	3.3	2E41	4.23	.09	4.91	8.67	55.36		.20	5	20	26	.22		.07			
762.6	764.4	82369	1.8	1.7	2D5	3.01	.08	1.69	5.93	17.11		.20	3	3	7	.27		.06			
0 764.4	769.4	82370	5.0	4.9	2A41	2.87	.13	1.03	2.89	21.15		.20	3	4	8	.24		.03			
1 769.4	773.2	82371	3.8	3.8	2A41	2.79	.07	1.40	3.25	20.53		.19	3	2	6	.40		.06			
773.2	778.0	82372	4.8	4.6	2A41	2.76	.03	1.08	2.89	13.38		.20	1	3	5	.35		.03			
778.0	782.7	82373	4.7	4.7	2A41	2.78	.04	.96	2.61	17.11		.21	1	6	7	.31		.04			
0 782.7	787.0	82374	4.3	4.3	2A0	2.76	.02	.74	1.88	12.13		.19	1	1	2	.40		.01			
787.0	791.9	82375	4.9	4.3	2A0	2.66	.02	1.30	2.46	23.02		.13	2		3	.27		.04			

DDH: 83F-04 UTM-N: 6357.4 UTM-E: 14356.4 UTM-ELEV: 4016.9 TOTAL DEPTH: 800.7 SECTION: 132+00E
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
~~0~~ 696.6	699.2	82376	2.6	2.6	1D4	2.81	.02	.33	.60	3.11		.05	2	2	4	.33		.07			
~~4~~ 699.2	703.2	82377	4.0	4.0	2A4	2.94	.05	1.34	3.05	23.95		.20	1	5	6	.22		.03			
~~6~~ 703.2	707.6	82378	4.4	4.4	2E41	3.61	.09	1.86	4.80	45.10		.21	2	19	22	.19		.04			
~~6~~ 707.6	710.5	82379	2.9	2.9	2E4	3.90	.14	5.47	8.83	95.49		.09	7	16	24	.19		.15			
~~5~~ 710.5	712.3	82380	1.8	1.6	2D0	2.88	.07	2.09	2.98	46.66		.12	3	3	6	.36		.03			
~~0~~ 712.3	716.4	82381	4.1	4.0	2D5	2.87	.06	1.04	2.64	35.77		.15	3	4	7	.27		.04			
~~7~~ 716.4	720.1	82382	3.7	3.7	2A14	2.82	.06	2.45	2.47	66.87		.26	5	2	7	.32		.06			
~~7~~ 720.1	723.8	82383	3.7	3.7	2A14	2.79	.06	1.39	2.89	40.12		.24	2	2	5	.27		.03			
~~X~~ 775.0	777.0	82384	2.0	2.0	2D0	2.89	.07	1.29	3.57	44.79		.01	7	1	9	.34		.09			
~~X~~ 789.6	790.8	82385	1.2	1.2	0Q9	2.86	.05	.09	.17	5.29		.03	4	4	9	.38		.07			
~~3~~ 792.8	793.5	82386	.7	.7	0Q9	2.92	.04	.12	.16	6.22		.01	7	3	10	.43		.09			
~~3~~ 794.5	795.6	82387	1.1	1.1	0Q9	2.96	.05	.03	.07	4.98		.01	5	4	10	.29		.08			

DDH: 83F-07 UTM-N: 6641.7 UTM-E: 15201.5 UTM-ELEV: 4013.7 TOTAL DEPTH: 202.0 SECTION: 132+100E
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
52.0	61.0	82388	9.0	2.3	2G4	4.41	.21	5.23	5.80	83.05		.19	3	19	23	13.13		.22			
6 61.0	64.5	82389	3.5	.7	2G4	4.23	.21	4.69	5.81	58.16		.12	4	18	23	14.34		.28			
4 64.5	68.0	82390	3.5	3.5	2A41	2.78	.08	1.50	3.35	22.08		.07		2	2	.56		.01			
6 68.0	72.0	82391	4.0	4.0	2A41	2.80	.13	2.10	4.00	28.62		.07	1	3	4	.73		.02			
6 72.0	76.0	82392	4.0	3.8	2A41	2.73	.07	2.28	4.05	25.19		.10	1	1	2	.66		.01			
4 76.0	80.0	82393	4.0	3.2	2A41	2.74	.09	1.27	3.67	14.93		.10	2	2	4	.35		.02			
6 80.0	87.0	82394	7.0	2.2	2A41	2.72	.22	2.51	6.51	28.62		.19	2	1	3	.32		.05			
5 87.0	90.4	82395	3.4	3.4	2A41	2.67	.08	1.27	4.01	18.35		.11	2	2	4	.56		.02			
0 90.4	97.0	82396	6.6	6.6	2A1	2.65	.05	.56	1.18	12.75		.08	2	1	3	.53		.01			

05MAR87 !THE IMPERIAL ANVIL!

ASSAY LISTING (DEPTH SEQUENCE) DH015

PAGE:218

DDH: 83F-08 UTM-N: 6125.0 UTM-E: 14587.4 UTM-ELEV: 4021.7 TOTAL DEPTH: 690.0 SECTION: 132+300E
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----								-----ASSAYS-----													
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
632.6	636.4	82397	3.8	3.8	2A41	2.74	.05	1.03	3.08	13.69		.09	2	4	6	.25		.06			
636.4	641.5	82398	5.1	5.1	2E4	3.87	.16	4.63	6.89	80.56		.13	6	14	21	7.01		.14			
641.5	645.5	82399	4.0	4.0	2A4&	2.70	.02	.65	1.68	12.75		.51	1	1	3	.29		.03			
645.5	648.2	82400	2.7	2.7	2D0	3.28	.07	3.28	6.85	53.81		.18	4	9	14	.32		.05			
648.2	652.0	82401	3.8	3.7	2A1	2.72	.04	1.33	2.23	26.44		.13	2	2	4	.29		.03			
652.0	655.0	82402	3.0	3.0	2A1	2.70	.02	.69	1.70	19.60		.51	1	1	3	.26		.03			

DDH: 83F-09 UTM-N: 6645.6 UTM-E: 15039.6 UTM-ELEV: 4018.1 TOTAL DEPTH: 493.0 SECTION: 132+300E
RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS----				-----ASSAYS-----																
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
238.4	240.6	82403	2.2	2.1	2A0	2.79	.05	.25	.41	11.82		.11	5	3	8	.19		.17		

DDH: 83F-10 UTM-N: 5689.5 UTM-E: 14541.0 UTM-ELEV: 3981.1 TOTAL DEPTH: 727.0 SECTION: 132+600E
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
352.1	355.3	82404	3.2	3.2	2L0&	2.82	.04	.35	.35	8.71		.02	2	3	5	.27		.06			
355.3	359.3	82405	4.0	4.0	2A0	2.79	.09	.74	1.79	18.05		.21	2	4	6	.19		.03			
359.3	364.9	82406	5.6	5.6	2A0&	2.82	.05	.65	2.36	17.11		.15	1	3	4	.20		.01			
364.9	370.5	82407	5.6	5.6	2A0&	2.77	.03	1.02	2.61	12.75		.25	1	3	4	.22		.01			
370.5	375.8	82408	5.3	5.2	2A0	2.75	.03	.98	2.48	23.02		.23	1	3	4	.26		.01			
375.8	381.0	82409	5.2	5.2	2A0	2.80	.02	.92	2.29	23.01		.16	1	4	6	.23		.01			
381.0	386.7	82410	5.7	5.7	2A0	2.69	.02	.44	.74	12.13		.11	1	1	2	.88		.03			
386.7	392.4	82411	5.7	5.6	2A0	2.66	.02	.47	.85	8.71		.14		1	2	.87		.01			
392.4	395.7	82412	3.3	3.3	2A0	2.79	.05	.53	1.19	5.60		.19	1	4	6	.75		.02			
395.7	399.1	82413	3.4	3.4	2A0	2.72	.02	.26	.38	3.11		.04	2	1	4	.73		.04			

DDH: 83F-11 UTM-N: 6517.8 UTM-E: 15193.3 UTM-ELEV: 4005.0 TOTAL DEPTH: 212.0 SECTION: 132+500E
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
39.0	40.8	82414	1.8	1.7	2A43	3.03	.05	4.90	9.65	25.19		.22	1	7	9	.15		.01			
40.8	44.0	82415	3.2	2.2	2D0	3.04	.22	.88	2.03	13.38		.16	3	9	13	.27		.02			
44.0	47.0	82416	3.0	3.0	2D0	3.01	.22	1.00	1.98	18.97		.16	3	9	13	.42		.03			
47.0	52.0	82417	5.0	.2	2D0	2.90	.12	.54	.96	10.58		.11	2	6	9	.62		.02			
52.0	56.0	82418	4.0	1.2	2E64	4.32	.29	7.40	6.71	142.14		.63	2	22	25	5.69		.26			
56.0	62.0	82419	6.0	.6	2E64	4.31	.36	8.08	6.69	146.19		.80	8	20	29	4.83		.34			
62.0	67.0	82420	5.0	4.0	2E64	4.31	.36	6.72	5.30	121.30		.26	8	22	30	3.07		.19			
67.0	72.0	82421	5.0	4.6	2E64	4.32	.21	6.34	6.80	88.33		.23	8	19	27	7.78		.17			
72.0	77.0	82422	5.0	3.9	2E64	4.28	.23	6.22	5.38	124.73		.53	10	20	30	4.74		.22			
77.0	80.0	82423	3.0	.8	2G0	4.47	.20	4.08	4.26	72.47		.58	2	22	25	15.26		.17			
80.0	85.0	82424	5.0	4.5	2G4	4.24	.20	5.08	5.11	59.10		.20	2	19	22	17.42		.18			
85.0	90.2	82425	5.2	4.5	2G4	4.11	.23	5.41	5.74	75.58		.14	2	22	24	10.62		.19			
90.2	95.0	82426	4.8	2.2	2A4	2.80	.05	1.71	3.23	21.46		.26		2	2	.87		.01			
95.0	100.0	82427	5.0	5.0	2A4	2.80	.05	1.35	3.24	27.37		.08	1	2	4	.76		.01			
100.0	105.0	82428	5.0	3.4	2A0	2.85	.05	.95	2.33	22.71		.08	1	3	4	.60		.01			
105.0	110.0	82429	5.0	4.0	2A0	2.72	.05	.89	1.98	24.88		.11	2	2	4	.77		.02			
110.0	116.0	82430	6.0	3.1	2A0	2.72	.03	.49	.91	20.22		.11	2	1	4	.41		.05			

DDH: 83F-12 UTM-N: 6860.6 UTM-E: 14280.4 UTM-ELEV: 4004.7 TOTAL DEPTH: 832.0 SECTION: 127+300E
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS---							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
736.6	738.6	82431	2.0	2.0	2H41	3.89	.19	5.12	8.79	82.11		.14	13	14	28	.40		.13			
738.6	742.2	82432	3.6	3.4	2E41	4.22	.11	5.50	9.53	81.49		.13	7	22	29	.18		.11			
742.2	744.2	82433	2.0	2.0	2E4&	3.96	.11	4.66	8.69	74.65		.13	4	21	26	.43		.09			
744.2	748.0	82434	3.8	3.5	2E4	4.25	.17	4.37	8.05	65.01		.12	7	23	30	.59		.27			
748.0	752.2	82435	4.2	4.2	2E4	3.87	.14	3.94	7.63	62.52		.25	6	19	25	.27		.13			
752.2	755.5	82436	3.3	3.3	2A34	3.19	.05	2.20	5.96	32.66		.41	3	10	14	.32		.04			
755.5	760.0	82437	4.5	3.1	2A34	2.94	.11	2.03	3.41	52.25		.65	4	4	9	.32		.04			
760.0	764.7	82438	4.7	4.2	2A34	2.79	.13	1.26	3.15	37.64		1.60	3	12	15	.26		.03			

DDH: 83F-14 UTM-N: 6750.3 UTM-E: 15309.6 UTM-ELEV: 3985.5 TOTAL DEPTH: 198.5 SECTION: 132+400E
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
9.7	15.0	82439	5.3	.9	2A0?	2.62	.01	.20	.37	9.64		.05				.56		.01			
15.0	22.0	82440	7.0	.7	2A0?	2.60	.01	.25	.16	8.71		.03				.48		.01			
22.0	26.0	82441	4.0	.4	2A0?	2.60	.06	.38	.40	8.09		.05			1	.66		.01			
26.0	30.0	82442	4.0	.4	2A0	2.60	.05	.51	.41	15.24		.14		1	1	.29		.01			
30.0	34.0	82443	4.0	1.4	2A0	2.69	.11	.58	1.33	15.86		.12		1	2	.42		.01			
34.0	38.2	82444	4.2	1.4	2A0	2.67	.11	.88	1.93	21.46		.10			1	.59		.02			
38.2	40.3	82445	2.1	2.1	2A1	2.67	.03	.37	.42	11.20		.05	2	1	4	.50		.02			
40.3	42.0	82446	1.7	1.7	2A11	2.83	.02	.31	.91	6.84		.29	4	2	6	.22		.16			
96.5	98.1	82447	1.6	1.4	0Q9	2.85	.12	.30	.63	17.73		.01	3	5	8	.19		.03			
98.1	102.8	82448	4.7	3.8	2A0	2.67	.04	.41	1.29	14.93		.05	1	1	2	.55		.03			
102.8	107.4	82449	4.6	4.6	2A0	2.70	.04	.37	.78	16.80		.47	1	1	2	.77		.03			
107.4	108.5	82450	1.1	1.1	0Q9	3.27	.10	12.03	.26	660.33		.07	2	7	10	.24		.03			

DDH: 83F-15 UTM-N: 7078.3 UTM-E: 14504.0 UTM-ELEV: 4013.0 TOTAL DEPTH: 759.0 SECTION: 127+300E
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
641.4	647.0	82451	5.6	5.6	2A4	2.94	.11	2.36	3.95	29.24		.27	3	3	7	.20		.02			
647.0	652.7	82452	5.7	5.5	2D0	2.90	.10	3.88	2.08	50.08		.55	3	2	5	.32		.02			
652.7	654.8	82453	2.1	2.0	2E46	4.33	.03	4.34	12.32	59.41		.14	2	24	27	4.60		.05			
654.8	660.6	82454	5.8	5.6	2G41	4.28	.12	4.55	7.50	74.65		.09	5	16	22	14.17		.20			
660.6	662.3	82455	1.7	1.7	2D4	3.72	.17	4.78	5.08	67.50		.19	9	9	18	10.53		.15			
662.3	666.5	82456	4.2	4.1	2F46	3.84	.19	4.49	6.85	87.10		.23	9	16	25	4.03		.16			
666.5	669.8	82457	3.3	3.3	2E48	4.51	.10	2.48	5.96	48.21		.10	7	28	36	.19		.05			
669.8	675.2	82458	5.4	5.3	2A41	3.03	.05	1.74	4.41	24.37		.12	4	3	7	.36		.02			
675.2	680.5	82459	5.3	5.1	2A41	2.81	.06	1.07	2.88	21.15		.14	3	2	6	.27		.01			
680.5	684.0	82460	3.5	3.4	2A38	2.90	.10	1.06	2.51	29.55		.27	2	5	7	.25		.01			
684.0	687.4	82461	3.4	3.4	2A0	2.82	.05	.53	1.75	9.95		.05	3	2	5	.24		.01			
687.4	689.4	82462	2.0	2.0	2A1	2.75	.06	.52	1.55	15.55		.08	3		3	.22		.02			
689.4	692.6	82463	3.2	3.1	2D5	2.87	.05	.97	2.73	24.26		.04	5	2	8	.28		.04			
692.6	695.7	82464	3.1	3.1	2D5	3.09	.14	1.60	3.50	34.34		.05	8	6	14	.35		.03			
695.7	700.0	82465	4.3	4.0	2A1	2.79	.05	.80	2.02	17.42		.04	2	2	4	.21		.01			
700.0	704.3	82466	4.3	4.1	2A1	2.82	.06	.91	2.04	29.55		.05	3	2	6	.20		.04			
704.3	708.6	82467	4.3	4.3	2A1	2.78	.03	.66	2.08	15.55		.04	2	1	3	.34		.02			
708.6	709.7	82468	1.1	1.1	2C0	2.85	.05	.62	.77	18.35		.05	3	3	7	.26		.13			

DDH: 83F-16 UTM-N: 6713.9 UTM-E: 15410.5 UTM-ELEV: 3984.9 TOTAL DEPTH: 196.0 SECTION: 132+500E
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
15.0	20.0	82469	5.0	5.0	2A0	2.67	.14	1.28	.54	15.55		.02			1	.77					
20.0	21.4	82470	1.4	1.4	2A0	2.69	.18	1.44	1.25	12.75		.01		1	1	.79					
21.4	25.0	82471	3.6	3.6	2A1	2.71	.12	1.30	1.44	12.13		.02	1	1	3	.72		.01			
25.0	28.9	82472	3.9	3.9	2L4	2.68	.13	.68	.47	8.71		.01	3		4	.77		.02			
28.9	33.8	82473	4.9	4.9	2A1	2.73	.11	.48	.73	10.25		.02	2	2	5	.87		.01			
33.8	37.5	82474	3.7	3.7	2A0	2.71	.04	.61	.63	9.02		.04	1	2	3	.60		.03			
37.5	39.0	82475	1.5	1.5	2A4	2.86	.05	.74	1.09	8.09		.02	3	3	6	.35		.11			
39.0	44.0	82476	5.0	5.0	2L4	2.75	.02	.40	.84	5.60		.04	3		4	.56		.09			
68.0	72.0	82477	4.0	3.4	2A0	2.78	.04	.62	.68	9.64		.02	4	1	5	.67		.09			
72.0	77.0	82478	5.0	5.0	2A0	2.77	.04	.76	1.91	14.31		.12	2	1	4	.72		.03			
77.0	81.5	82479	4.5	4.4	2A0	2.80	.04	.64	1.95	18.04		.10	3	2	5	.75		.03			
81.5	86.0	82480	4.5	4.3	2D5	2.94	.05	1.68	3.10	35.77		.09	4	3	8	.53		.05			
86.0	90.0	82481	4.0	3.4	2A1	2.82	.04	.93	2.13	16.49		.07	3	1	5	.66		.04			
90.0	95.0	82482	5.0	5.0	2D5	2.88	.07	1.18	2.54	18.66		.14	3	3	7	.34		.05			
95.0	100.6	82483	5.6	5.4	2L4	2.88	.05	.97	2.42	18.35		.01	5	3	9	.39		.08			
100.6	102.7	82484	2.1	2.0	2A0	2.82	.06	.29	.74	6.84		.01	3	3	7	.29		.04			
109.2	109.8	82485	.6	.6	2E34	3.50	.08	3.64	6.54	73.72		.05	5	18	23	.19		.17			

DDH: 83F-17 UTM-N: 6650.4 UTM-E: 15501.8 UTM-ELEV: 3986.9 TOTAL DEPTH: 200.0 SECTION: 132+600E
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
9.5	12.0	82486	2.5	2.5	2A0	2.66	.03	1.01	.12	21.77		.03				1.04		.01			
12.0	15.0	82487	3.0	3.0	2A0	2.64	.02	.80	.08	10.26		.03				1.03					
15.0	19.0	82488	4.0	4.0	2A0	2.61	.02	.63	.12	12.44		.05				1.37					
19.0	24.0	82489	5.0	5.0	2A0	2.62	.05	.56	.10	9.95		.07				1.13					
24.0	29.0	82490	5.0	5.0	2A0	2.67	.07	.73	.45	15.86		.04			1	1.02					
29.0	31.8	82491	2.8	2.8	2A0	2.70	.05	.49	.50	7.78		.03			1	.70					

DDH: 83F-18 UTM-N: 6573.2 UTM-E: 15274.2 UTM-ELEV: 4006.5 TOTAL DEPTH: 171.0 SECTION: 132+500E
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
24.0	28.5	82492	4.5	9	2L07	2.66	.03	.76	.30	44.79		.80	4		4	.70		.01			
28.5	31.2	82493	2.7	2.7	1E19	2.70	.01	.20	.09	9.02		.31		3	4	.25		.01			
31.2	36.0	82494	4.8	4.8	2F4	3.12	.10	6.84	8.18	44.48		.27	1	5	7	.33		.01			
36.0	40.4	82495	4.4	4.2	2G4	4.45	.25	5.50	4.53	93.93		.24		23	24	11.63		.11			
40.4	42.0	82496	1.6	1.6	2G4	4.25	.18	3.84	6.28	72.16		.18	3	17	20	18.74		.20			
42.0	47.0	82497	5.0	5.0	2H4	4.32	.35	5.68	6.72	108.86		.38	13	17	31	8.63		.31			
47.0	51.5	82498	4.5	4.5	2H4	4.54	.21	4.66	5.78	84.60		.58	10	21	31	8.41		.34			
51.5	57.5	82499	6.0	6.0	2H4	4.40	.27	5.60	6.24	84.60		.41	18	11	30	8.46		.38			
57.5	61.4	82500	3.9	3.9	2E46	4.22	.23	4.62	5.09	75.29		.22	9	22	31	4.16		.30			
61.4	65.0	82501	3.6	3.6	2D6	3.43	.07	2.82	4.00	51.32		.34	2	13	16	9.11		.11			
65.0	69.7	82502	4.7	4.7	2B46	3.04	.23	2.66	1.67	39.19		.22	2	5	8	8.64		.06			
69.7	72.9	82503	3.2	3.2	2E46	4.28	.14	5.91	5.48	78.69		.21	4	24	29	5.15		.18			
72.9	74.0	82504	1.1	1.1	2A14	3.05	.08	5.60	6.30	57.23		.34	1	2	4	1.22		.03			
74.0	80.4	82505	6.4	6.4	2A0	2.80	.05	1.14	1.87	25.82		.58		1	2	1.18		.01			
80.4	84.9	82506	4.5	4.5	2D5	2.82	.05	1.72	3.00	26.75		.20	1	1	3	.69		.02			
84.9	90.2	82507	5.3	5.3	2D0&	2.85	.06	1.44	2.38	32.04		.24		2	3	.73		.01			
90.2	95.0	82508	4.8	4.8	2A4	2.86	.04	1.35	2.53	30.17		.38	1	2	3	.73		.01			
95.0	99.2	82509	4.2	4.2	2A4	2.80	.03	1.16	2.79	21.15		.25		3	4	.68		.01			
99.2	103.5	82510	4.3	4.3	2A0	2.83	.08	.90	2.28	17.11		.26	1	4	5	.90		.01			
103.5	107.8	82511	4.3	4.3	2A0	2.75	.04	.49	.76	15.86		.14	1	1	3	.68		.01			
107.8	109.5	82512	1.7	1.7	2A0&	2.77	.02	1.62	2.20	31.10		.14	1		2	.55		.05			

DDH: 83F-19 UTM-N: 7346.4 UTM-E: 14193.2 UTM-ELEV: 3988.6 TOTAL DEPTH: 787.0 SECTION: 122+600E
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
694.5	697.9	82513	3.4	3.4	2A41	2.74	.04	.85	2.51	20.84	0-1	.05	5	3	8	.25		.05			
697.9	699.5	82514	1.6	1.6	2D4	3.23	.11	4.84	7.16	68.12		.05	9	6	16	.20		.08			
699.5	704.1	82515	4.6	4.6	2E41	3.66	.18	6.47	10.64	96.11		.09	14	9	24	.18		.14			
704.1	708.7	82516	4.6	4.6	2E41	3.38	.09	8.57	16.20	114.15		.09	10	3	14	.14		.15			
708.7	713.2	82517	4.5	4.0	2E46	3.51	.12	7.51	13.90	101.71		.07	12	5	18	1.35		.16			
713.2	717.5	82518	4.3	4.3	2H41	3.87	.22	5.96	11.00	90.82	>6	.07	21	7	28	1.65		.15			
717.5	721.8	82519	4.3	4.3	2H41	3.72	.26	4.00	8.97	66.56		.08	24	7	31	.61		.11			
721.8	726.0	82520	4.2	4.2	2H41	3.63	.20	5.13	10.16	78.38		.12	20	6	26	.81		.08			
726.0	728.0	82521	2.0	1.4	2E41	3.83	.06	4.08	7.81	45.10		.12	5	21	26	.20		.05			
728.0	732.7	82522	4.7	4.3	2A43	2.82	.07	1.06	2.70	21.46	0-1	.22	3	5	9	.21		.02			
732.7	735.9	82523	3.2	3.2	2A0	2.76	.07	.64	1.46	16.80		.11	4	2	6	.22		.02			

DDH: 83F-20 UTM-N: 6482.3 UTM-E: 15145.2 UTM-ELEV: 4005.4 TOTAL DEPTH: 197.0 SECTION: 132+500E
RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS---				-----ASSAYS-----																
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
116.5	122.0	82524	5.5	5.5	2A0	2.79	.04	.72	1.45	15.24		.10	3	1	4	.36		.11		

DDH: 83F-22 UTM-N: 7143.7 UTM-E: 13992.6 UTM-ELEV: 3989.6 TOTAL DEPTH: 917.0 SECTION: 122+600
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----		-----ASSAYS-----																			
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
834.4	838.0	33501	3.6	3.3	2A41	2.87	.03	2.16	2.94	27.37	5-6	.10	4	3	7	.14		.05			
838.0	842.4	33502	4.4	3.4	2A1	2.93	.06	1.16	2.77	25.82	0-4	.10	4	4	8	.18		.03			
842.4	843.0	33503	.6	.6	2D4	3.45	.11	6.96	11.03	118.82		.10	8	5	13	.09		.09			
843.0	845.3	33504	2.3	2.0	2H41	3.91	.20	4.65	7.85	94.24		.10	20	6	26	.20		.09			
845.3	846.3	33505	1.0	1.0	2A41	3.17	.06	2.57	4.46	37.95	>6	.10	10	3	13	.28		.06			
846.3	848.9	33506	2.6	2.5	2F4&	4.41	.09	3.50	7.70	46.66		.10	10	21	32	.10		.03			
848.9	851.8	33507	2.9	2.9	2D05	2.99	.06	1.58	3.51	25.50	5-6	.10	4	2	7	.25		.02			
851.8	855.4	33508	3.6	3.6	2A1&	2.85	.05	.80	2.26	17.42		.20	4	2	6	.14		.02			
855.4	860.0	33509	4.6	4.6	2A1&	2.81	.04	1.03	2.41	18.66		.20	3	3	6	.11		.02			
860.0	865.1	33510	5.1	4.9	2A1&	2.99	.07	.97	2.79	23.64	0-4	.30	3	4	7	.16		.02			
865.1	868.1	33511	3.0	3.0	2Q0	3.05	.13	1.65	2.58	53.19		.80	5	4	10	.14		.03			

DDH: 84F-01 UTM-N: 9090.3 UTM-E: 14515.3 UTM-ELEV: 3810.0 TOTAL DEPTH: 516.0 SECTION: 119+000
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

-----DEPTHS-----						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
283.0	286.3	33512	3.3	3.3	2C39	3.21	.50	.20	.29	10.89		.20	6	11	18	.23			.03		
286.3	291.2	33513	4.9	4.9	2D09	3.44	.27	2.49	6.08	36.70		.30	5	10	15	.14			.07		
291.2	295.7	33514	4.5	4.5	2D49	3.61	.30	4.19	10.95	59.72		.30	13	4	17	.37			.16		
295.7	301.5	33515	5.8	5.6	2G4	4.50	.17	5.34	5.88	88.25		.20	6	19	26	11.50			.38		
301.5	305.7	33516	4.2	4.2	2G4	4.69	.22	5.32	5.98	71.54		.30	6	17	23	15.00			.35		
305.7	308.9	33517	3.2	3.2	2G4	4.65	.19	5.62	5.88	88.33		.40	6	19	26	13.51			.32		
308.9	312.2	33518	3.3	3.2	2E46	4.31	.26	5.09	6.65	94.56		.20	15	12	27	6.23			.30		
312.2	317.4	33519	5.2	5.2	2L2	2.99	.09	1.20	1.55	31.10		.30	3	3	7	4.51			.09		
317.4	322.6	33520	5.2	4.2	2B06	2.96	.05	.82	1.11	20.84		.10	3	1	4	6.38			.07		
322.6	326.8	33521	4.2	4.2	2B06	2.88	.06	.81	.50	32.04		.28	2	2	5	5.91			.07		
326.8	330.0	33522	3.2	3.0	2B06	3.24	.11	2.84	2.76	78.38		.20	6	4	11	8.20			.16		
330.0	335.6	33523	5.6	5.6	2E14	3.54	.18	2.97	3.12	55.99		.20	8	10	19	3.65			.18		
338.0	341.1	33600	3.1	3.1	2B0	3.04	.08	1.00	1.12	29.24		.40	2	3	6	3.84			.06		
348.2	355.0	33601	6.8	4.6	1E19	2.73	.07	.51	.42	16.17		.60	2	1	4	3.46			.07	.18	
355.0	359.6	33602	4.6	4.1	2L14	3.03	.22	1.96	6.09	94.56		4.66	4	3	7	3.26			.25	.30	
359.6	364.2	33603	4.6	4.0	2L14	3.03	.39	2.04	.91	149.61		17.56	3	5	8	3.30			.09	.91	
364.2	367.5	33524	3.3	3.3	2D09	3.21	.26	3.79	2.43	330.64		18.36	6	5	11	4.59			.14	.63	
367.5	372.0	33525	4.5	4.5	2E46	4.68	.19	4.90	6.15	53.81		.10	3	24	27	6.74			.08		
372.0	375.0	33526	3.0	3.0	2G4	4.53	.10	5.07	7.87	53.50		.01	2	12	15	28.29			.09		
375.0	380.1	33527	5.1	5.1	2E09	4.60	.58	2.95	4.94	31.10		.01	5	27	32	.34			.12		
380.1	385.0	33528	4.9	4.7	2E09	4.69	.32	4.59	7.83	38.57		.10	4	26	30	.06			.10		
385.0	389.9	33529	4.9	4.9	2E4	4.77	.14	4.23	7.05	25.50		.10	3	27	31	.02			.08		
389.9	391.5	33530	1.6	1.6	2E4	4.63	.16	6.09	9.77	41.68		.01	4	25	29	.11			.10		
391.5	397.0	33531	5.5	4.9	2E4	4.76	.28	2.57	2.01	41.99		.10	2	31	34	.02			.09		
397.0	403.4	33532	6.4	5.8	2E4	4.35	.10	3.74	3.53	55.05		.10	2	27	30	.03			.10		
403.4	407.0	33533	3.6	3.6	2E0&	4.66	.13	2.07	1.48	22.39		.01	2	32	35	.02			.06		
407.0	412.3	33534	5.3	4.6	2E4&	4.52	.14	2.61	2.05	20.22		.10	3	29	32	.01			.07		
412.3	416.4	33535	4.1	4.1	2E4&	4.51	.18	2.58	2.30	21.15		.01	3	29	32	.01			.09		
416.4	421.4	33536	5.0	4.8	2E4&	4.68	.30	1.35	2.84	13.37		.01	3	30	34	.01			.09		
421.4	425.2	33537	3.8	3.8	2E0&	4.43	.22	2.15	1.46	19.28		.10	3	28	31	.01			.09		
425.2	430.1	33538	4.9	4.9	2E42	4.80	.16	2.88	4.60	22.70		.01	3	30	33	.01			.06		
430.1	433.9	33539	3.8	3.8	2E42	4.92	.19	3.42	6.12	27.37		.01	1	30	32	.02			.02		
433.9	438.0	33540	4.1	4.1	2E42	4.81	.08	3.32	5.45	23.33		.10	1	31	32	.02			.02		
438.0	441.1	33541	3.1	3.0	2E42	4.60	.11	1.56	4.09	14.93		.01	2	30	33	.02			.04		
441.1	446.0	33542	4.9	4.9	2E09	4.60	.64	1.00	2.74	14.31		.01	5	29	34	.01			.10		
446.0	450.2	33543	4.2	3.9	2E49	4.78	.24	1.87	4.38	14.62		.01	3	30	33	.02			.06		
450.2	454.0	33544	3.8	3.7	2E4	4.73	.05	3.32	5.97	19.28		.01	2	29	32	.01			.03		
454.0	459.1	33545	5.1	5.1	2E44	4.36	.29	3.94	7.39	37.95		.10	6	23	30	.03			.07		
459.1	462.7	33546	3.6	3.6	2D09	3.17	.24	4.12	5.32	30.79		.10	5	3	9	.16			.04		
462.7	466.0	33547	3.3	3.3	2A1	2.80	.07	1.06	2.48	13.69		.01	3	1	5	.42			.02		
466.0	468.4	33548	2.4	2.4	2D0	3.18	.16	2.21	5.60	35.77		.01	7	5	13	.13			.03		
468.4	471.3	33549	2.9	2.9	2A1	3.01	.13	.57	1.47	12.75		.01	5	5	11	.11			.05		

DDH: 84F-02 UTM-N: 7557.8 UTM-E: 13989.6 UTM-ELEV: 3985.5 TOTAL DEPTH: 855.0 SECTION: 122+300E
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
778.9	781.0	33550	2.1	2.1	2L12	2.88	.03	.17	.24	5.60		.10	2	2	4	.24		.06			
781.0	786.7	33551	5.7	5.7	2A4	3.00	.05	1.28	2.73	26.44		.10	3	2	5	.14		.03			
786.7	789.8	33552	3.1	2.7	2D0	3.33	.15	2.42	4.42	41.37		.10	9	8	17	.15		.05			
789.8	790.5	33553	.7	.7	2E43	3.84	.17	3.13	5.64	58.47		.10	13	16	29	.04		.07			
790.5	793.0	33554	2.5	2.4	2D0	3.15	.13	3.58	4.84	51.32		.10	5	4	10	.15		.03			
793.0	797.0	33555	4.0	4.0	2A4	2.99	.08	1.23	3.15	15.24		.10	5	5	10	.20		.03			
797.0	801.6	33556	4.6	4.0	2A4	2.98	.05	1.79	3.10	22.39		.10	4	3	8	.16		.01			
801.6	804.0	33557	2.4	2.4	2A0	2.90	.08	.95	2.57	21.46		.10	4	3	7	.17		.02			
804.0	809.0	33558	5.0	4.6	1D49	2.73	.02	.06	.14	2.49		.10	5		5	.22		.05			

DDH: 84F-03 UTM-N: 9277.7 UTM-E: 14732.1 UTM-ELEV: 3791.7 TOTAL DEPTH: 381.0 SECTION: 119+000
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

-----DEPTHS----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
154.9	161.7	33559	6.8	6.6	2E14	3.70	.22	2.32	3.53	47.59			.10	12	14	26	3.96				.10
174.8	179.0	33560	4.2	4.2	2D39	3.54	.22	2.03	5.00	46.34			.10	11	10	22	3.29				.16
179.0	184.3	33561	5.3	4.2	2L2	3.17	.18	1.64	1.42	37.95			.10	8	9	17	4.90				.14
184.3	189.3	33562	5.0	4.9	2E49	4.23	.30	4.56	3.67	97.36			.20	12	21	34	1.07				.26
189.3	191.4	33563	2.1	2.1	2E4	4.70	.17	3.99	4.52	51.01			.20	2	33	35	.13				.05
191.4	196.0	33564	4.6	4.5	2E4&	4.32	.15	1.92	2.51	22.39			.10	4	30	35	.04				.14
196.0	200.0	33565	4.0	3.9	2E09	4.58	.39	1.92	2.69	38.26			.10	8	30	38	.03				.25
200.0	203.6	33566	3.6	3.5	2E09	4.45	.25	1.86	1.79	29.86			.10	7	29	37	.08				.24
203.6	206.7	33567	3.1	2.6	2E41	4.54	.17	6.65	6.13	76.20			.20	2	29	31	.09				.06
206.7	212.0	33568	5.3	2.6	2E0&	4.62	.26	1.97	2.18	22.08			.10	3	34	37	1.01				.10
212.0	216.0	33569	4.0	4.0	2E0&	4.49	.21	1.19	2.65	16.80			.10	3	31	35	.03				.10
216.0	220.4	33570	4.4	4.4	2E4	4.42	.17	2.14	4.23	20.84			.10	2	31	34	.43				.08
220.4	225.7	33571	5.3	5.3	2E89	4.41	.28	.57	1.02	3.42			.10	9	29	39	.01				.35
225.7	230.0	33572	4.3	4.3	2E09	4.59	.40	.30	1.16	4.66			.10	5	33	39	.01				.16
230.0	235.0	33573	5.0	5.0	2E4	4.45	.17	2.22	3.46	18.04			.10	3	31	34	.01				.06
235.0	240.4	33574	5.4	5.4	2E49	4.55	.20	3.18	6.12	18.97			.10	4	31	36	.02				.12
240.4	242.7	33575	2.3	2.1	2F49	4.53	.22	7.85	13.32	30.48			.10	7	23	31	.02				.42
242.7	247.9	33576	5.2	5.2	2E1	4.21	.13	.31	1.33	10.26			.10	2	31	34	.02				.03
247.9	250.4	33577	2.5	2.5	2E1	3.84	.12	.13	.84	10.89			.10	2	26	29	.01				.04
250.4	252.7	33599	2.3	2.0	2E4	4.28	.19	3.11	8.48	13.06			.10	6	23	29	.01				.29
252.7	257.4	33578	4.7	4.7	2E89	4.03	.63	.62	2.68	11.20			.10	7	28	35	.01				.24
257.4	262.0	33579	4.6	4.6	2E89	4.58	.63	.48	1.80	14.31			.10	7	31	38	.01				.22
262.0	264.5	33580	2.5	2.5	2E89	4.33	.48	.44	2.26	7.15			.10	9	29	38	.01				.30
264.5	269.1	33581	4.6	4.6	2E4	4.68	.09	4.99	9.15	26.75			.40	2	31	33	.01				.03
269.1	272.0	33582	2.9	2.9	2D35	3.46	.11	1.16	4.95	14.00			.10	2	16	18	.07				.03
272.0	274.7	33583	2.7	2.7	2A1	2.96	.08	.54	1.49	16.48			.20	2	8	10	.20				.03
274.7	278.0	33584	3.3	3.2	2D0&	2.95	.08	3.68	5.51	35.46			.10	3	2	5	.18				.04
278.0	281.3	33585	3.3	3.2	2C0&	2.41	.21	.49	1.84	14.93			.20	4	8	12	.20				.02
281.3	286.7	33586	5.4	5.0	2C37	3.94	.55	1.46	3.26	22.39			.10	19	14	33	.10				.03
286.7	289.4	33587	2.7	2.7	2C5	3.59	.06	.20	1.17	5.91			.10	1	23	24	.03				.01
289.4	291.9	33588	2.5	2.5	2D5	3.56	.14	2.28	4.91	35.15			.10	1	20	21	.04				.02
291.9	295.8	33589	3.9	3.7	2C5	3.29	.09	1.11	.74	17.73			.10	1	18	20	.03				.02
295.8	299.0	33590	3.2	3.2	2D4	3.42	.08	7.39	20.60	25.50			.20	4	4	8	.16				.02
299.0	305.0	33591	6.0	6.0	2D4	3.38	.09	6.78	17.70	41.99			.10	4	6	10	.11				.08
305.0	307.0	33592	2.0	2.0	2C0	3.15	.19	.58	1.94	9.02			.10	6	9	15	.15				.04
307.0	309.0	33593	2.0	1.9	2A1	2.89	.11	1.00	1.74	21.15			.10	3	3	7	.25				.02
309.0	314.0	33594	5.0	5.0	2A41	2.89	.07	2.80	4.24	38.26			.60	2	3	5	.18		.15		.02
314.0	318.7	33595	4.7	4.7	2A41	2.76	.06	1.52	4.87	23.64			.40	1	1	3	.21		.09		.02
318.7	324.0	33596	5.3	5.3	2A41	2.85	.06	1.51	3.18	27.37			.60	1	2	4	.17		.14		.01
324.0	329.5	33597	5.5	5.5	2A1	2.79	.09	.67	2.05	15.24			.20	2	3	5	.18				.01
329.5	333.8	33598	4.3	4.1	2A41	2.76	.07	1.75	4.76	19.91			.10	2	1	4	.17				.06

DDH: 84F-04 UTM-N: 7355.1 UTM-E: 13783.6 UTM-ELEV: 3960.3 TOTAL DEPTH: 923.0 SECTION: 122+300E
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
840.9	847.9	33729	7.0	7.0	2A0&	3.00	.05	1.34	3.72	21.15		.10	4	2	6	.17		.05			
847.9	850.1	33730	2.2	2.2	1F4@	2.97	.06	1.24	4.26	22.08		.10	8	3	12	.58		.05			
850.1	851.8	33731	1.7	1.7	2E43	3.58	.10	4.80	12.60	75.58		.10	12	7	19	1.04		.12			
851.8	854.0	33732	2.2	2.1	1F@	2.80	.05	.25	.33	5.91		.10	4	2	7	1.00		.06			
854.0	856.9	33733	2.9	2.9	2B4	2.86	.03	1.26	3.14	21.46		.10	2	1	4	.47		.02			
856.9	860.0	33734	3.1	2.8	2A14	3.02	.05	1.60	3.33	29.24		.30	4	1	6	.38		.02			
860.0	862.8	33735	2.8	2.8	2B4	2.96	.07	3.01	4.83	86.78		.80	4	2	7	.21		.04			
862.8	864.4	33736	1.6	1.6	1F4@	3.13	.11	5.21	6.43	139.97		.30	9	3	13	.11		.08			
864.4	865.9	33737	1.5	1.2	2E43	3.93	.22	6.47	8.63	206.53		.40	9	16	26	.02		.10			
865.9	868.8	33738	2.9	2.7	1F4@	2.97	.06	.80	1.81	19.91		.10	10	1	12	.16		.06			
868.8	872.2	33739	3.4	3.4	2E34	3.75	.22	1.98	3.38	49.45		.10	13	17	30	.10		.08			
872.2	875.5	33740	3.3	3.3	0Q0	2.90	.06	.11	.20	3.42		.10	3	2	6	.18		.04			
875.5	877.7	33741	2.2	2.1	2A0	2.82	.05	.85	1.66	22.39		.30	3	3	6	.13		.02			
877.7	880.1	33742	2.4	1.6	2C0	2.91	.07	.56	1.13	10.57		.30	3	3	6	.10		.03			

DDH: 84F-05 UTM-N: 9442.8 UTM-E: 14851.5 UTM-ELEV: 3776.6 TOTAL DEPTH: 460.0 SECTION: 119+000
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

-----DEPTHS-----						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
24.0	29.8	33641	5.8	5.6	2D43	3.75	.12	3.52	6.78	69.36		.80	3	16	20	8.66		.05			
29.8	33.8	33642	4.0	4.0	2L0	2.84	.07	.36	.17	8.09		1.60	4	1	5	.69		.03			
33.8	36.5	33643	2.7	2.7	2D43	3.49	.26	4.42	10.78	101.90		.40	5	12	17	.13		.06			
36.5	40.0	33644	3.5	3.5	2H49	4.21	.56	4.25	6.97	126.90		.20	34	3	38	.03		.03			
40.0	42.8	33645	2.8	2.8	2D43	3.50	.24	4.50	9.48	125.66		.60	6	10	17	.30		.06			
69.4	74.7	33646	5.3	5.3	2D3	3.45	.12	1.98	6.29	17.11		.10	3	14	18	.90		.09			
74.7	78.7	33647	4.0	4.0	2E08	4.58	.13	1.73	2.30	18.97		.10	1	35	36	3.30		.01			
78.7	79.9	33648	1.2	1.2	2F4	4.45	.05	9.27	16.90	75.27		.10	3	23	26	.06		.03			
79.9	83.0	33649	3.1	3.0	2E49	4.75	.23	1.73	2.52	17.42		.10	1	38	39	.02		.02			
83.0	86.7	33650	3.7	3.6	2E0	4.77	.19	1.30	1.22	17.11		.10	1	39	40	.07		.01			
86.7	90.6	33651	3.9	3.9	2E09	4.44	.34	.16	.29	10.57		.10	1	37	39	.03		.02			
90.6	94.2	33652	3.6	3.4	2D35	3.24	.12	1.50	4.78	31.42		.80	1	14	15	.14		.03			
94.2	98.0	33653	3.8	3.7	2E09	4.46	.34	.15	.37	9.95		.10	1	37	39	.01		.03			
98.0	101.8	33654	3.8	3.8	2E09	4.16	.23	.14	.68	5.29		1.00	2	33	36	.02		.07			
101.8	105.0	33655	3.2	3.2	2E08	4.13	.24	1.51	1.73	8.40		.10	7	28	35	.03		.26			
105.0	110.0	33656	5.0	5.0	2E48	4.36	.25	1.62	3.00	8.09		.10	9	28	37	.02		.22			
110.0	115.0	33657	5.0	5.0	2E48	4.02	.35	1.90	3.09	12.13		.10	12	27	39	.07		.28			
115.0	120.0	33658	5.0	5.0	2E08	3.68	.48	1.26	.72	34.84		1.00	7	19	27	.62		.19			
120.0	125.7	33659	5.7	5.6	2E08	3.59	.26	.09	1.41	2.80		.10	6	28	34	.11		.10			
125.7	128.8	33660	3.1	3.1	2E09	4.45	.35	.04	.47	3.73		.10	1	37	39	.02		.03			
128.8	131.7	33661	2.9	2.9	2E1	4.04	.13	.14	.74	5.29		.10	1	31	32	.04		.02			
131.7	133.5	33662	1.8	1.7	2E41	3.90	.11	5.96	6.44	21.77		.20	2	23	26	.03		.02			
133.5	137.3	33663	3.8	3.8	2E0	3.62	.12	.28	.44	6.84		.20	2	27	30	.09		.02			
137.3	141.0	33664	3.7	3.6	2D39	3.45	.28	3.26	5.11	68.74		2.00	2	15	17	.07		.05			
141.0	145.0	33665	4.0	4.0	2C3	3.59	.12	.27	.20	16.48		.40	1	23	25	.03		.01			
145.0	150.1	33666	5.1	5.1	2C3	3.48	.11	1.89	1.08	74.03		.40	1	19	21	.04		.05			
150.1	154.2	33667	4.1	4.1	2D45	3.42	.09	3.26	7.82	29.86		.80	1	14	16	.08		.03			
154.2	158.0	33668	3.8	3.8	2C3	3.57	.06	.45	.90	7.46		.20		24	24	.06		.01			
158.0	162.3	33669	4.3	4.1	2C39	3.91	.20	.18	1.03	2.49		.10	3	27	30			.11			
162.3	166.3	33670	4.0	4.0	2E09	3.80	.20	.37	2.04	4.04		.10	6	22	29			.17			
166.3	171.3	33671	5.0	5.0	2E49	3.91	.20	2.19	3.47	4.04		.10	8	20	28	.01		.22			
171.3	173.8	33672	2.5	2.5	2E81	4.09	.20	.47	2.13	3.11		.10	8	34	42			.22			
173.8	180.0	33673	6.2	5.7	2E81	4.03	.25	.40	1.38	3.42		.10	7	33	40	.02		.18			
180.0	185.0	33674	5.0	4.9	2E89	4.20	.61	.09	1.12	2.49		.10	10	25	35			.27			
185.0	190.0	33675	5.0	5.0	2E89	4.41	.31	.15	2.01	4.04		.10	11	26	38			.33			
190.0	195.0	33676	5.0	5.0	2E19	4.08	.53	.67	.58	9.64		.10	4	26	31	.01		.15			
195.0	200.0	33677	5.0	5.0	2E89	4.37	.78	1.01	2.31	10.88		.10	9	36	45			.30			
200.0	205.0	33678	5.0	4.8	2E89	4.02	.66	1.00	.99	20.22		.30	3	27	30	.01		.09			
205.0	209.0	33679	4.0	4.0	2E89	4.47	.39	.10	.98	10.57		.10	6	31	38	.01		.22			
209.0	215.0	33680	6.0	5.8	2E09	4.25	.58	.14	.95	14.62		.10	1	33	34	.02		.04			
215.0	220.0	33681	5.0	5.0	2E09	4.44	.52	.88	2.22	14.00		.10	2	31	34	.01		.07			
220.0	225.0	33682	5.0	5.0	2E08	4.26	.17	.15	1.49	7.15		.10	2	32	34	.01		.07			
225.0	230.0	33683	5.0	5.0	2E08	4.27	.17	.14	1.98	6.22		.10	2	31	33	.01		.08			
230.0	235.0	33684	5.0	5.0	2C3	4.07	.08	1.18	3.95	10.89		.10	1	28	30	.01		.04			
235.0	239.0	33685	4.0	4.0	2C3	3.96	.04	.77	1.96	8.71		.10	1	28	29	.03		.03			
239.0	243.2	33686	4.2	4.1	2C3	3.96	.04	1.07	.56	8.09		.10		29	29	.03		.02			
243.2	248.0	33687	4.8	4.8	2D43	3.49	.06	3.42	8.23	23.02		.10	2	17	20	.06		.03			
248.0	252.0	33688	4.0	3.7	2D43	3.57	.05	3.58	10.79	26.13		.10	2	17	20	.04		.03			
252.0	255.3	33689	3.3	3.2	2E4	4.49	.03	3.00	6.55	25.50		.10	1	32	33	.01		.03			
255.3	258.0	33690	2.7	2.7	2D0	3.13	.12	1.48	2.63	15.86		.10	6	6	12	.23		.03			

DDH: 84F-05 UTM-N: 9442.8 UTM-E: 14851.5 UTM-ELEV: 3776.6 TOTAL DEPTH: 460.0 SECTION: 119+000
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

							-----ASSAYS-----													
-----DEPTHS----	SAMPLE	INT.	REC.	ROCK	S.G.	Cu	Pb	Zn	Ag(AA)	Ag(FA)	Au(FA)	Po	Py	TOT	BaO	Hg	Mn	As	Ba	S.G.
FROM TO NO.	NO.			UNIT	PULP	%	%	%	g/mT	g/mT	g/mT	%	%	Fe	%	%	%	%	%	W.R.
258.0	261.7	33691	3.7	3.4	2C0	2.93	.17	.26	.25	5.91		.20	3	5	9	.28				.02
261.7	265.0	33692	3.3	3.0	2D5	2.95	.08	1.52	3.73	18.04		.30	2	4	6	.30				.03
265.0	271.3	33693	6.3	6.3	2C35	3.29	.07	.74	2.16	18.04		.30	2	14	16	.14				.02
271.3	275.0	33694	3.7	3.7	2C3	3.36	.05	.94	2.40	19.28		.40	2	15	17	.14				.02
275.0	279.0	33695	4.0	4.0	2D3	3.14	.07	1.10	2.95	23.33		.30	3	7	11	.17				.03
279.0	283.0	33696	4.0	4.0	2D0	2.96	.08	1.45	3.42	18.66		.30	4	4	8	.21				.04
283.0	285.9	33697	2.9	2.8	2D0	2.99	.07	1.41	3.08	22.39		.30	3	5	9	.17				.04
285.9	289.0	33698	3.1	3.1	2A13	3.14	.05	1.02	2.76	23.95		.30	1	11	13	.17				.02
289.0	294.0	33699	5.0	4.6	2A13	3.03	.05	.28	.64	12.75		.30	1	9	11	.20				.02
294.0	299.0	33700	5.0	4.6	2C0&	3.07	.07	.96	1.14	21.77		.10	3	8	11	.30				.03
299.0	305.2	33701	6.2	6.2	2C0&	3.00		.74	1.82	18.35		.10	3	5	8	.23				.03
305.2	309.0	33702	3.8	3.8	2D5	2.85	.07	1.56	3.80	20.22		.50	1	2	4	.25				.02
309.0	314.0	33703	5.0	5.0	2A13	2.96	.06	.50	1.61	15.55		.10	1	6	8	.23				.02
314.0	319.0	33704	5.0	5.0	2A13	3.00	.07	.16	.10	9.02		.10	3	7	11	.21				.02
319.0	324.2	33705	5.2	5.2	2A13	2.97	.16	.13	.05	12.13		.10	5	7	12	.18				.02
324.2	330.4	33706	6.2	6.2	2C7	3.13	.19	.58	.35	20.84		.10	11	6	17	.13				.02
330.4	333.0	33707	2.6	2.5	2A13	2.97	.05	1.31	.05	13.37		.50	2	7	9	.21				.02
333.0	336.0	33708	3.0	3.0	2A13	2.92	.05	.30	1.53	28.62		.30	2	9	11	.22				.02
336.0	339.9	33709	3.9	3.9	2A13	2.87	.05	.22	1.88	9.02		.10	4	3	7	.20				.02
339.9	344.5	33710	4.6	4.5	2C7	3.02	.15	.28	.87	19.60		.10	11	1	13	.18				.02
344.5	349.0	33711	4.5	4.5	2C7	3.19	.19	.49	.28	12.44		.10	14	3	17	.17				.02
349.0	353.3	33712	4.3	3.3	2C79	3.04	.22	.77	.12	15.55		.10	11		11	.13				.02
353.3	359.0	33713	5.7	5.7	2C7&	2.98	.11	.22	.06	5.91		.10	11		11	.20				.02
359.0	364.0	33714	5.0	5.0	2C7&	3.02	.16	.14	.04	4.98		.10	9	3	12	.18				.03
364.0	369.6	33715	5.6	5.5	2C79	3.39	.29	.38	.23	10.57		.10	21		22	.13				.03
369.6	372.8	33716	3.2	3.2	2C79	3.33	.29	.30	.58	10.57		.10	14	5	19	.16				.03
372.8	376.0	33717	3.2	3.2	2D0	3.48	.16	3.83	4.65	60.03		.30	8	4	12	.13				.04
376.0	378.5	33718	2.5	2.5	2D4	3.37	.13	6.90	8.81	102.95		.50	7	3	10	.06				.05
378.5	383.3	33719	4.8	4.5	2L2	3.13	.08	2.72	.46	63.45		.10	6	2	8	.18				.04
383.3	386.8	33720	3.5	3.5	2L2	2.85	.11	.23	.09	5.29		.10	6	4	10	.24				.04
386.8	391.8	33721	5.0	5.0	2A1	2.84	.06	1.04	1.72	15.86		.10	3	2	5	.18				.04
391.8	396.7	33722	4.9	4.8	2A14	2.82	.04	1.18	3.95	13.37		.10	3	2	5	.20				.04
396.7	399.7	33723	3.0	2.7	0Q9	3.04	.12	12.65	.98	286.16		.80	3	2	6	.06				.04
399.7	403.0	33724	3.3	3.3	2B09	3.05	.20	1.79	.58	39.81		.30	4	4	8	.11				.03
403.0	407.0	33725	4.0	3.9	2D0&	2.80	.11	2.41	4.11	29.24		.10	4	3	7	.08				.03
407.0	411.2	33726	4.2	4.2	2L2	2.89	.06	1.11	2.14	13.68		.10	2	1	3	.16				.07
411.2	414.5	33727	3.3	3.3	2B4&	2.94	.08	2.17	2.82	26.75		.10	3	2	5	.10				.06
414.5	417.0	33728	2.5	2.5	2B0&	2.82	.05	1.15	1.26	17.73		.10	3	1	5	.11				.05

DDH: 84F-06 UTM-N: 9295.8 UTM-E: 14499.3 UTM-ELEV: 3690.4 TOTAL DEPTH: 301.0 SECTION: 118+000
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

-----DEPTHS-----		-----ASSAYS-----																			
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
121.8	126.2	33743	4.4	4.4	2D43	3.36	.20	3.99	10.02	60.03		.10	7	8	16	.03		.14			
126.2	130.7	33744	4.5	4.2	2D03	3.60	.29	2.68	5.55	54.74		.10	9	14	24	.03		.19			
130.7	134.0	33745	3.3	1.3	2E48	4.29	.29	4.88	6.60	88.65		.10	13	19	33	.36		.38			
134.0	138.6	33746	4.6	4.0	2E0&	4.31	.38	1.95	1.62	35.15		.10	5	30	35	.07		.15			
138.6	143.6	33747	5.0	4.4	2E42	4.68	.26	4.06	4.09	54.43		.10	1	35	37	.02		.04			
143.6	148.4	33748	4.8	3.7	2E42	4.67	.31	3.65	3.36	32.04		.10	3	32	36	.01		.10			
148.4	152.0	33749	3.6	3.6	2E48	4.70	1.09	1.72	2.30	18.66		.10	6	31	38	.01		.20			
152.0	155.6	33750	3.6	3.6	2E48	4.76	.44	3.54	3.03	69.05		.10	11	27	39	.10		.29			
155.6	158.7	33751	3.1	3.1	2F4	5.02	.13	4.65	9.68	27.68		.10	2	30	33	.01		.07			
158.7	161.8	33752	3.1	2.8	2F4	4.65	.09	8.05	15.90	63.45		.10	3	24	27	.01		.06			
161.8	165.3	33753	3.5	3.4	2E0&	4.66	.26	2.94	4.03	33.28		.10	5	31	36			.17			
165.3	170.3	33754	5.0	5.0	2E0&	4.66	.26	1.91	2.45	23.02		.10	5	32	37	.01		.20			
170.3	175.3	33755	5.0	5.0	2E0&	4.64	.23	3.52	4.30	46.34		.10	5	30	35			.29			
175.3	177.9	33756	2.6	2.6	2F4	4.63	.08	14.00	22.00	122.55		.10	5	15	21	.06		.17			
177.9	179.8	33757	1.9	1.9	2E87	4.50	.31	5.01	4.97	89.58		.10	15	21	36	.08		.20			
179.8	179.9	90001	.1	.1	FUDGE	2.75															
179.9	180.9	33758	1.0	1.0	2K8	3.73	.11	1.82	1.47	23.33		.10	33	1	35	.06		.90			
180.9	184.0	33759	3.1	3.0	2E89	4.52	1.11	1.09	2.23	17.42		.10	7	30	37	.02		.19			
184.0	187.9	33760	3.9	3.9	2J88	4.30	.19	4.49	3.97	72.16		.10	39	3	43	.14		.16			
187.9	191.8	33761	3.9	3.9	2J88	4.32	.08	1.66	2.22	67.18		.10	46	3	49	.03		.15			
191.8	195.7	33762	3.9	3.9	2J88	4.40	.22	4.12	3.60	29.24		.10	40	3	44	.03		.17			
195.7	201.1	33763	5.4	5.4	2J88	4.18	.11	5.66	4.93	20.53		.10	41	1	42	.03		.17			
201.1	206.5	33764	5.4	5.2	2J88	4.30	.69	4.85	3.94	40.12		.10	33	6	39	.02		.23			
206.5	211.8	33765	5.3	5.2	2J88	4.11	.17	4.15	4.83	19.91		.10	35	4	39	.03		.21			
211.8	215.3	33766	3.5	3.5	2D49	3.15	.30	2.04	4.42	29.24		.10	5	6	12	.14		.09			
215.3	218.7	33767	3.4	3.4	2D4&	3.05	.13	2.75	6.11	32.97		.10	4	4	8	.27		.11			
218.7	221.8	33768	3.1	3.1	2A1	2.85	.10	.39	.98	9.64		.10	4	3	7	.13		.10			
252.2	255.1	33769	2.9	2.8	2Q0	2.96	.15	1.54	3.05	35.15		.10	4	5	9	.11		.06			
255.1	259.5	33770	4.4	4.4	2C79	3.24	.43	.31	.43	23.64		.30	12	8	21	.16		.06			
259.5	263.9	33771	4.4	4.4	2C79	2.81	.13	.23	.10	48.21		4.30	3	2	6	.28		.05			
285.0	289.8	33632	4.8	4.6	0Q9	2.78	.10	4.38	.10	41.99		.10	1	1	2	.06		.02			
289.8	294.6	33633	4.8	4.8	0Q9	3.01	.26	13.00	.10	202.49		5.00	1	1	2	.04		.03			

DDH: 84F-07 UTM-N: 6374.3 UTM-E: 14799.6 UTM-ELEV: 4009.2 TOTAL DEPTH: 626.0 SECTION: 132+300E
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
6 563.8	566.3	33636	2.5	2.5	2E49	3.89	.22	5.00	8.61	83.98		.20	9	16	25	.11		.16			
5 566.3	570.3	33637	4.0	4.0	2D0	3.04	.10	1.62	3.97	33.90		.10	4	5	10	.06		.07			
6 570.3	574.2	33638	3.9	3.9	2D0	3.14	.11	1.37	4.67	28.30		.10	6	7	13	.09		.07			
5 574.2	579.2	33639	5.0	4.7	2A0	2.85	.08	1.55	3.85	36.08		.20	3	3	7	.24		.04			
0 579.2	583.3	33640	4.1	4.0	2A0	2.85	.05	.80	1.86	20.53		.10	3	2	5	.21		.06			

DDH: 84F-08 UTM-N: 9597.3 UTM-E: 14999.4 UTM-ELEV: 3758.7 TOTAL DEPTH: 280.0 SECTION: 119+000
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

-----DEPTHS-----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
43.2	49.2	33604	6.0	6.0	2C39	3.53	.21	.90	1.21	31.10		.60	5	18	23	.08		.06			
49.2	54.7	33605	5.5	5.5	2D3	3.69	.07	1.28	3.48	19.60		.40	1	22	24	.06		.01			
54.7	56.8	33606	2.1	2.1	2D43	3.51	.12	4.13	9.84	35.77		.20	6	10	17	.08		.10			
56.8	61.5	33607	4.7	4.7	2C37	3.18	.35	.80	1.53	13.37		.10	12	7	19	.07		.09			
90.2	92.5	33608	2.3	2.3	2E19	3.66	.23	.12	.51	7.78		.10	3	23	27	.02		.03			
92.5	97.5	33609	5.0	5.0	2D3	3.36	.14	1.57	4.17	17.73		.10	3	14	18	.07		.03			
97.5	102.5	33610	5.0	5.0	2D3	3.19	.11	2.68	5.57	23.02		.10	3	11	15	.06		.03			
102.5	107.5	33611	5.0	5.0	2A43	3.36	.06	5.19	8.62	46.97		.40	2	13	15	.08		.01			
107.5	112.5	33612	5.0	4.6	2A43	3.33	.07	2.61	5.86	29.24		.20	2	14	16	.07		.02			
112.5	117.5	33613	5.0	4.7	2A43	3.35	.07	2.95	7.56	34.52		.40	1	14	16	.06		.01			
117.5	122.5	33614	5.0	5.0	2A43	3.60	.05	1.66	5.43	23.33		.10	1	19	21	.09		.01			
122.5	128.3	33615	5.8	5.3	2A43	3.38	.05	1.85	5.44	21.46		.10	2	14	16	.11		.01			
128.3	131.2	33616	2.9	2.9	2D35	3.46	.03	2.40	7.09	26.75		.20	1	15	17	.10		.01			
131.2	137.6	33617	6.4	6.4	2A43	3.37	.04	2.48	5.73	27.68		.40	1	15	17	.09		.01			
137.6	140.7	33618	3.1	3.1	2A3	3.15	.05	.53	2.15	11.20		.10	1	15	16	.13		.01			
140.7	146.7	33619	6.0	6.0	2D35	3.34	.08	1.11	3.29	17.11		.10	2	18	21	.09		.02			
146.7	152.0	33620	5.3	5.3	2D35	3.22	.08	.93	4.57	19.28		.10	4	11	15	.15		.02			
152.0	157.0	33621	5.0	5.0	2A13	3.01	.06	.23	.61	14.93		.10	4	11	15	.11		.04			
157.0	162.0	33622	5.0	5.0	2A41	3.36	.06	1.42	3.63	27.06		.20	2	14	16	.08		.02			
162.0	168.1	33623	6.1	6.1	2A41	3.27	.05	1.69	4.89	27.68		.10	2	13	15	.11		.02			
168.1	172.0	33624	3.9	3.7	2A13	3.07	.08	.29	.31	14.00		.10	5	9	14	.15		.01			
172.0	175.2	33625	3.2	3.2	2A13	3.09	.04	.33	1.54	13.37		.10	1	13	14	.13		.01			
175.2	180.2	33626	5.0	5.0	2C0	3.29	.13	.52	1.14	13.06		.10	5	12	17	.05		.02			
180.2	185.6	33627	5.4	5.4	2C0	3.51	.11	.24	1.76	9.95		.10	9	13	22	.11		.01			
185.6	190.2	33628	4.6	4.6	2C5	3.56	.06	.30	1.40	11.82		.20	7	18	25	.10		.01			
190.2	195.2	33629	5.0	5.0	2A13	3.04	.08	.40	1.37	13.06		.10	3	10	14	.20		.01			
195.2	200.2	33630	5.0	5.0	2A13	3.18	.07	.67	1.05	18.35		.20	3	14	18	.11		.01			
200.2	204.6	33631	4.4	4.4	2A13	3.16	.09	.24	1.71	12.13		.20	5	13	18	.16		.01			
204.6	209.0	33634	4.4	4.4	2H9	4.10	.33	1.08	4.90	24.26		.10	35	3	39	.01		.02			
209.0	214.1	33635	5.1	5.1	2D09	3.09	.21	1.51	3.93	27.37		.20	6	5	12	.16		.02			

DDH: 84F-09 UTM-N: 6504.6 UTM-E: 14501.2 UTM-ELEV: 4020.6 TOTAL DEPTH: 814.0 SECTION: 132+000E
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
6 747.1	751.0	33772	3.9	3.8	2D4	3.36	.13	5.14	9.20	116.64		.40	7	7	14	.09		.12			
0 751.0	753.9	33773	2.9	2.9	2A1	2.79	.15	.39	.87	9.33		.10	4	4	8	.21		.04			
6 753.9	756.3	33774	2.4	2.4	2D09	3.37	.22	2.94	5.83	50.70		.30	7	11	18	.08		.10			
6 756.3	759.6	33775	3.3	3.3	2D0	2.89	.09	4.08	3.41	74.96		.30	3	3	6	.22		.05			
0 759.6	763.0	33776	3.4	3.4	2B0	2.69	.06	.76	1.67	16.48		.10	2	1	3	.30		.03			
6 763.0	767.7	33777	4.7	4.7	2A41	2.99	.08	5.22	3.69	110.73		.50	2	2	5	.24		.05			
4 767.7	772.5	33778	4.8	4.8	2A41	2.74	.05	1.15	2.86	21.15		.10	2	1	3	.15		.04			

DDH: 84F-10 UTM-N: 7362.1 UTM-E: 14790.8 UTM-ELEV: 3886.3 TOTAL DEPTH: 525.0 SECTION: 127+300E
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
400.9	403.0	33779	2.1	2.0	2D49	3.18	.38	4.47	6.80	60.96		.30	5	9	14	.10		.12			
403.0	405.8	33780	2.8	2.7	2G48	4.62	.49	4.54	5.40	67.50		.10	10	22	33	4.15		.29			
405.8	409.5	33781	3.7	3.6	2F49	4.72	.22	4.68	5.97	64.07		.10	5	26	31	.10		.19			
409.5	412.7	33782	3.2	3.2	2G4	4.35	.18	5.16	5.92	82.11		.10	8	18	26	6.88		.27			
412.7	415.9	33783	3.2	3.1	2G4	4.61	.11	4.80	5.10	93.93		.10	6	23	30	4.41		.32			
415.9	417.3	33784	1.4	1.4	2G47	4.37	.22	5.01	5.99	87.71		.10	11	17	28	5.14		.26			
417.3	422.0	33785	4.7	4.4	2D0	3.11	.11	1.42	4.49	25.19		.10	3	5	8	.20		.06			
422.0	426.7	33786	4.7	4.7	2D0	2.95	.08	1.85	4.53	30.17		.10	3	3	7	.11		.06			
426.7	430.9	33787	4.2	3.8	2A1&	2.88	.05	.78	1.80	15.55		.10	2	2	4	.30		.03			
430.9	435.1	33788	4.2	3.9	2A1&	2.91	.06	1.24	2.28	23.64		.10	2	4	7	.29		.04			
435.1	438.5	33789	3.4	3.4	2B5	2.88	.08	.88	1.86	25.82		.10	4	3	7	.22		.04			
438.5	442.0	33790	3.5	3.0	2D5	3.00	.08	1.85	3.48	33.59		.10	3	3	6	.23		.04			
442.0	447.2	33791	5.2	3.4	2A41	3.12	.09	3.27	4.03	69.98		.10	6	5	11	.20		.09			
447.2	451.5	33792	4.3	3.9	2A0	2.75	.05	.64	1.72	12.44		.10	2	1	3	.54		.03			
451.5	454.8	33793	3.3	2.0	2B5	2.82	.07	.97	2.00	19.91		.10	2	2	4	.36		.03			
454.8	458.2	33794	3.4	3.4	2B45	2.98	.07	3.96	2.07	90.51		.10	2	3	5	.31		.04			
458.2	463.9	33795	5.7	5.6	2A03	2.89	.10	1.97	1.13	27.99		.10	3	4	8	.17		.12			
463.9	469.5	33796	5.6	5.3	2A03	2.79	.05	.13	.22	2.49		.10	2	2	5	.40		.16			
469.5	475.2	33797	5.7	5.7	2A03	2.84	.10	.64	.41	43.55		.40	2	2	4	.36		.10			

DDH: 84F-13 UTM-N: 7054.9 UTM-E: 15127.6 UTM-ELEV: 3872.5 TOTAL DEPTH: 210.0 SECTION: 132+052E
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
~~5~~ 71.1	74.4	33810	3.3	3.3	2D0	3.21	.18	1.10	4.51	19.91		.26	3	8	12	.31		.05			
~~6~~ 74.4	79.9	33811	5.5	5.3	2D0	3.63	.14	4.09	5.33	62.83		.11	6	13	20	.34		.19			
~~0~~ 79.9	84.6	33812	4.7	4.6	2A1	2.91	.07	.98	1.71	21.15		.03	2	3	5	.69		.03			
	84.6	33813	5.0	5.0	2D3&	3.17	.08	2.02	5.63	44.48		.04	4	4	8	.18		.04			
~~6~~ 89.6	95.0	33814	5.4	5.4	2A41	3.09	.08	1.13	5.07	23.33		.07	4	4	8	.37		.03			
	95.0	33815	4.3	4.1	2A41	2.90	.05	.83	2.97	18.66		.11	3	2	5	.51		.03			
	99.3	33816	5.0	5.0	2A0	2.86	.04	1.26	2.67	22.71		.13	2	1	4	.82		.03			
~~0~~ 104.3	108.0	33817	3.7	3.7	2B0	2.73	.05	.38	1.00	9.33		.03	2	2	4	.79		.02			
	108.0	33818	2.4	2.4	2B0	2.80	.07	.43	.84	12.75		.13	2	3	5	.68		.02			
	110.4	33819	5.0	2.2	2B0	2.80	.06	.75	2.27	18.35		.08	2	3	5	.63		.02			
~~6~~ 115.4	120.4	33820	5.0	2.7	2D0	3.00	.09	1.51	5.39	27.68		.07	5	5	10	.30		.05			
~~5~~ 120.4	124.9	33821	4.5	4.5	2D0	2.80	.08	2.12	3.56	41.06		.05	3	2	6	.43		.04			
~~0~~ 124.9	129.0	33822	4.1	4.0	1E19	2.60	.05	.49	1.29	10.58		.05	2	2	4	.57		.10			
~~8~~ 174.1	179.7	33823	5.6	5.5	0Q9	3.17	.32	2.68	4.79	93.62		.07	7	7	14	.15		.06			
~~6~~ 179.7	183.5	33824	3.8	3.4	2L14	2.80	.28	.97	2.36	47.28		.50	6	1	7	.27		.05			

DDH: 84F-14 UTM-N: 7186.1 UTM-E: 15019.7 UTM-ELEV: 3870.6 TOTAL DEPTH: 335.0 SECTION: 131+022E
RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS----				-----ASSAYS-----																
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
228.5	231.5	33825	3.0	2.8	2A1	3.24	.18	1.44	3.14	37.32		.05	8	8	17	.42		.05		

DDH: 84F-17 UTM-N: 7287.9 UTM-E: 15117.1 UTM-ELEV: 3871.1 TOTAL DEPTH: 227.0 SECTION: 131+022E
 RFE: S2 RFE DIR: 210 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 0

-----DEPTHS-----						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
127.0	130.0	33798	3.0	3.0	2A0	3.17	.19	.34	.38	12.44		.25	2	10	13	.64		.03			
130.0	133.4	33799	3.4	3.4	2A33	3.35	.50	.30	.28	19.91		.42	4	15	20	.22		.04			
133.4	137.0	33800	3.6	3.6	2D0	3.40	.18	.42	5.17	13.06		.45	3	11	14	.29		.04			
137.0	139.7	33801	2.7	2.7	2D4	3.44	.10	4.13	12.60	40.44		.43	3	9	12	.31		.03			
139.7	141.6	33802	1.9	1.9	2F43	4.05	.12	5.50	6.94	85.22		.21	7	18	26	1.04		.25			
141.6	146.5	33803	4.9	4.9	2D0&	2.92	.08	1.70	2.90	24.26		.08	2	2	5	.17		.06			
146.5	153.1	33804	6.6	6.6	2D0&	2.86	.04	1.71	2.68	26.13		.03	3	2	5	.41		.06			
153.1	154.4	33805	1.3	1.3	2Q9	3.81	.21	5.93	8.35	101.09		.05	7	12	20	.33		.14			
154.4	160.7	33806	6.3	6.0	2B0	2.94	.07	.58	1.23	11.51		.02	3	3	6	4.34		.03			
160.7	164.7	33807	4.0	4.0	2E43	3.91	.21	3.13	7.39	58.16		.05	10	14	25	2.39		.12			
164.7	170.8	33808	6.1	4.1	2C0	3.08	.09	.99	2.31	23.02		.03	4	5	10	.66		.04			
170.8	175.2	33809	4.4	4.2	2A0	2.83	.03	.52	.92	9.33		.02	2	1	3	.91		.03			

DDH: 84F-18 UTM-N: 8715.3 UTM-E: 14518.6 UTM-ELEV: 3915.6 TOTAL DEPTH: 585.0 SECTION: 121+000
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

-----DEPTHS-----						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
379.9	383.2	33826	3.3	3.3	2C39	3.33	.57	.61	.18	21.27		.31	6	13	20	.22		.04			
383.2	386.0	33827	2.8	2.6	2D39	3.17	.26	2.00	5.83	41.68		1.20	5	6	12	.18		.05			
386.0	389.6	33828	3.6	3.5	2D39	3.41	.39	1.54	8.85	29.55		.45	13	4	17	.63		.15			
389.6	391.0	33829	1.4	1.4	2H41	4.13	.50	4.75	7.46	74.03		.19	24	7	31	.30		.32			
391.0	396.0	33830	5.0	5.0	2E46	4.68	.05	4.61	6.79	64.07		.20	2	28	31	3.09		.29			
396.0	400.0	33831	4.0	4.0	2G4	4.64	.16	4.63	5.64	55.37		.22	2	23	26	8.55		.27			
400.0	405.4	33832	5.4	5.4	2G4	4.65	.14	5.24	6.07	90.82		.27	7	18	25	11.48		.37			
405.4	409.5	33833	4.1	4.1	2H49	4.30	.30	5.11	7.46	65.63		.09	20	10	30	.54		.27			
420.4	424.0	33834	3.6	3.6	2H43	4.28	.29	5.62	8.42	71.85		.07	18	11	30	.70		.20			
424.0	426.9	33835	2.9	2.9	2H43	4.44	.28	6.03	7.34	91.45		.08	14	17	32	.76		.20			
426.9	432.0	33836	5.1	5.0	2H43	4.45	.31	5.03	6.69	76.20		.13	35	1	37	2.31		.19			
432.0	437.0	33837	5.0	5.0	2H43	4.41	.31	5.96	7.62	93.31		.06	23	9	33	2.32		.20			
437.0	441.0	33838	4.0	4.0	2K43	4.20	.27	4.09	5.15	59.41		.05	17	14	32	.26		.14			
441.0	444.0	33839	3.0	3.0	2K43	4.16	.29	4.53	6.18	65.32		.05	17	12	30	.20		.12			
444.0	447.8	33840	3.8	3.6	2H43	4.39	.30	5.96	9.11	86.16		.06	25	5	30	.28		.11			
447.8	450.5	33841	2.7	2.7	2G4	4.59	.11	4.18	5.81	59.72		.05	5	19	24	13.49		.08			
450.5	453.6	33842	3.1	3.1	2G4	4.68	.14	4.19	5.98	40.12		.04	1	18	20	20.69		.05			
453.6	457.4	33843	3.8	3.8	2E09	4.89	.31	1.35	.76	16.49		.03	1	36	37	.52		.02			
457.4	461.0	33844	3.6	3.6	2E46	4.74	.46	3.27	4.93	32.35		.04	1	25	27	10.07		.03			
461.0	464.8	33845	3.8	3.6	2E46	4.73	.22	2.11	3.19	143.08		.05	2	31	33	3.54		.03			
464.8	468.0	33846	3.2	3.2	2G49	4.73	.20	5.95	7.28	51.94		.04	2	21	23	10.46		.05			
468.0	471.5	33847	3.5	3.5	2G4	4.71	.13	4.84	7.12	56.30		.08	2	12	14	26.72		.06			
471.5	477.2	33848	5.7	5.7	2E46	4.71	.24	3.01	3.32	33.28		.04	3	30	34	1.15		.06			
477.2	483.3	33849	6.1	6.1	2E49	4.65	.23	2.74	4.90	30.48		.05	3	30	33	.29		.08			
483.3	488.3	33850	5.0	5.0	2E09	4.52	.54	1.72	1.69	42.30		.15	5	30	35	.17		.20			
488.3	492.6	33851	4.3	3.7	2E09	4.59	.90	1.53	1.27	35.46		.10	3	23	27	.15		.17			
492.6	495.0	33852	2.4	2.4	2E09	4.49	.26	1.84	1.90	25.82		.06	4	25	30	.15		.19			
495.0	501.0	33853	6.0	6.0	2E4	4.55	.19	4.19	6.12	37.01		.03	3	28	31	.15		.05			
501.0	506.4	33854	5.4	5.4	2E4	4.76	.09	4.96	9.70	39.19		.03	2	28	30	.15		.02			
506.4	512.0	33855	5.6	5.6	2E49	4.79	.37	3.07	4.43	32.97		.03	2	32	34	.15		.04			
512.0	517.0	33856	5.0	4.7	2E4	4.80	.18	2.15	4.58	34.53		.05	4	31	35	.16		.04			
517.0	520.4	33857	3.4	3.4	2E4	4.81	.11	2.32	4.81	28.30		.10	3	32	35	.15		.06			
520.4	523.1	33858	2.7	2.6	2D09	3.21	.27	2.81	4.01	62.21		.09	4	7	11	.30		.03			
523.1	528.4	33859	5.3	5.1	2D39	3.13	.21	1.37	2.83	28.93		.07	4	8	12	.35		.03			
528.4	533.5	33860	5.1	5.1	2D39	3.02	.13	1.44	5.22	37.32		.21	4	6	10	.31		.03			
533.5	539.4	33861	5.9	5.9	2A0	2.81	.27	1.15	2.05	33.28		.11	3	2	5	.26		.04			

DDH: 84F-19 UTM-N: 8896.6 UTM-E: 14700.0 UTM-ELEV: 3913.8 TOTAL DEPTH: 597.0 SECTION: 121+000
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

-----DEPTHS-----						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
339.3	340.4	33862	1.1	1.1	1E19	2.75	.07	.11	.18	6.84			.05	3	2	5	.50				.04
340.4	345.5	33863	5.1	5.0	2E19	3.48	.41	.09	.26	14.62			.14	6	16	23	.21				.09
345.5	348.6	33864	3.1	3.1	2D43	3.58	.09	1.95	14.10	35.77			.15	4	12	17	.24				.10
348.6	351.6	33865	3.0	3.0	2H46	4.35	.28	4.55	7.04	76.83			.13	18	11	30	5.73				.23
351.6	357.4	33866	5.8	5.8	2H46	4.14	.28	4.90	8.79	81.18			.11	21	8	30	3.00				.29
357.4	359.9	33867	2.5	2.5	2G07	4.40	.25	3.09	5.40	57.54			.07	24	2	27	18.47				.15
359.9	362.0	33868	2.1	2.0	2H69	4.30	.32	3.36	6.24	67.81			.13	39		39	1.19				.20
362.0	366.6	33869	4.6	4.4	2L14	3.30	.10	3.35	3.27	68.12			.05	8	6	15	3.85				.14
366.6	370.8	33870	4.2	4.2	2L14	2.77	.04	.32	.46	11.82			.11	4	3	8	3.24				.07
370.8	375.8	33871	5.0	5.0	2L14	2.73	.04	.12	.27	7.78			.10	4	3	7	2.25				.06
375.8	378.5	33872	2.7	2.7	2E41	3.86	.09	3.58	9.08	57.85			.07	7	16	23	2.64				.13
378.5	380.8	33873	2.3	2.3	2H43	4.38	.25	5.82	9.97	86.16			.08	27	9	36	.30				.12
380.8	384.0	33874	3.2	3.0	2G47	4.34	.16	4.50	8.98	59.41			.10	13	9	22	21.12				.10
384.0	386.2	33875	2.2	2.2	2K47	3.99	.19	7.52	12.00	103.58			.09	15	12	27	1.47				.15
386.2	390.0	33876	3.8	3.8	2L14	2.98	.07	.73	.97	13.69			.06	4	4	9	5.61				.04
390.0	391.8	33877	1.8	1.8	2Q96	3.90	.13	4.62	8.80	99.53			.09	10	16	26	2.94				.21
391.8	393.9	33878	2.1	2.1	2H06	2.96	.12	.87	1.12	17.11			.02	4	3	7	4.41				.03
393.9	398.6	33879	4.7	4.7	2H49	4.14	.31	5.33	7.78	98.60			.07	29	9	38	1.03				.30
398.6	400.0	33880	1.4	1.4	1H4	2.92	.14	1.12	1.95	18.97			.03	9	6	15	3.39				.18
400.0	402.0	33881	2.0	2.0	2E4*	4.26	.20	7.33	9.39	129.08			.09	12	14	27	5.36				.39
402.0	403.0	33882	1.0	1.0	1H4	2.91	.08	1.54	1.04	21.15			.03	10		11	2.56				.15
403.0	406.5	33883	3.5	3.5	2E46	4.09	.25	4.47	12.00	85.23			.09	15	12	28	4.05				.40
406.5	408.4	33884	1.9	1.8	2L14	3.07	.18	.51	.57	14.00			.03	14	2	16	5.21				.14
408.4	409.2	33885	.8	.8	2E36	3.74	.36	1.87	1.53	45.41			.17	8	21	30	2.92				.21
409.2	410.5	33886	1.3	1.3	2B06	2.87	1.04	.57	.99	39.19			.66	2	4	7	4.16				.09
410.5	412.7	33887	2.2	2.2	2E46	4.11	.26	3.70	2.81	81.18			.10	8	24	32	1.16				.31
412.7	414.7	33888	2.0	1.6	1H4	2.85	.12	1.42	.40	41.06			1.65	8	4	13	3.07				.10
414.7	421.0	33889	6.3	6.3	1H4	2.99	.24	1.43	.35	50.08			1.17	7	5	13	3.75				.14
421.0	422.8	33890	1.8	1.8	2E46	4.02	.27	1.77	2.32	45.72			.22	8	24	33	2.40				.22
422.8	425.8	33891	3.0	2.3	2D63	3.69	.15	.77	2.12	32.04			.62	4	16	21	11.08				.13
425.8	429.3	33892	3.5	3.5	2G4	4.46	.07	5.25	9.03	93.00			.25	2	3	6	26.53				.09
429.3	433.8	33893	4.5	4.5	2G4	4.47	.29	4.45	4.79	73.72			.25	5	3	9	7.41				.12
433.8	438.8	33894	5.0	5.0	2E0&	4.56	.11	.96	.92	17.11			.10	1	35	37	.26				.06
438.8	443.8	33895	5.0	5.0	2E0&	4.62	.23	2.14	1.53	37.32			.06	1	36	38	.16				.06
443.8	447.0	33896	3.2	3.2	2E0&	4.55	.18	2.18	1.48	34.53			.07		35	36	.31				.01
447.0	452.0	33897	5.0	5.0	2E1	3.96	.04	.42	.23	9.95			.08		29	29	.61				.01
452.0	456.2	33898	4.2	4.2	2E1	4.30	.09	1.86	2.95	27.99			.09	2	24	27	3.54				.04
456.2	461.2	33899	5.0	5.0	2D0&	3.30	.25	4.54	3.44	51.63			.08	6	7	14	.72				.05
461.2	467.4	33900	6.2	6.1	2D0&	3.03	.27	1.37	3.31	24.57			.15	6	5	11	.50				.05
467.4	469.1	33901	1.7	1.7	1H4	2.91	.58	.94	1.90	92.07			3.33	4	4	8	.47				.06
469.1	474.0	33902	4.9	4.9	2D09	3.03	.27	1.15	3.44	68.12			.54	5	5	11	.58				.05
474.0	478.0	33903	4.0	4.0	2E48	4.56	.20	1.72	3.02	20.84			.12	4	29	33	.17				.11
478.0	481.3	33904	3.3	3.3	2E48	4.66	.29	1.73	2.83	10.89			.05	7	26	34	.14				.22
481.3	485.5	33905	4.2	4.2	2E4	4.60	.13	1.99	5.69	9.95			.07	3	28	31	.36				.06
485.5	489.8	33906	4.3	4.3	2G49	4.46	.24	3.99	9.08	21.15			.05	4	19	23	9.26				.16
489.8	494.6	33907	4.8	4.8	2E49	4.43	.25	3.01	6.21	18.97			.03	5	24	30	.41				.17
494.6	501.1	33908	6.5	6.5	2E49	4.53	.22	5.65	6.57	36.08			.03	5	22	27	1.12				.14
501.1	505.0	33909	3.9	3.9	2G48	4.57	.18	6.33	10.39	59.10			.05	5	16	21	10.71				.22
505.0	509.8	33910	4.8	4.8	2E4	4.58	.26	3.76	5.17	35.46			.04	5	23	28	5.68				.19
509.8	514.8	33911	5.0	5.0	2E49	4.46	.30	2.11	3.93	22.40			.04	7	24	32	.29				.23
514.8	519.8	33912	5.0	5.0	2E49	4.38	.31	1.89	3.20	17.11			.03	8	23	32	.17				.24

DDH: 84F-19 UTM-N: 8896.6 UTM-E: 14700.0 UTM-ELEV: 3913.8 TOTAL DEPTH: 597.0 SECTION: 121+000
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

-----DEPTHS-----						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
519.8	524.8	33913	5.0	5.0	2E8&	4.45	.19	1.18	2.80	12.75		.03	10	23	33	.15		.25			
524.8	529.0	33914	4.2	4.2	2E48	4.69	.19	4.13	5.93	49.46		.03	6	24	30	.16		.25			
529.0	534.0	33915	5.0	4.0	2E4	4.50	.10	5.13	6.21	66.87		.04	4	22	27	.18		.17			
534.0	539.0	33916	5.0	4.9	2E4	4.51	.17	2.10	4.27	27.06		.03	4	27	31	.23		.06			
539.0	544.0	33917	5.0	4.9	2E4	4.51	.40	2.20	3.97	24.57		.04	7	25	32	.17		.07			
544.0	548.0	33918	4.0	3.8	2E4	4.88	.06	4.08	6.16	20.53		.03	1	28	30	.15		.03			
548.0	552.4	33919	4.4	4.4	2E4	4.73	.07	3.00	5.74	16.80		.06	1	28	30	.16		.02			
552.4	553.1	33920	.7	.7	1H4	3.29	.12	1.42	1.94	11.20		.03	4	13	17	.44		.06			
553.1	558.7	33921	5.6	5.6	2E4	4.71	.19	2.74	5.39	20.53		.04	3	28	31	.16		.03			
558.7	561.7	33922	3.0	3.0	2D0	3.19	.13	1.95	4.44	21.46		.03	5	7	12	.28		.07			
561.7	565.8	33923	4.1	4.1	2D0	2.91	.08	1.64	4.40	25.19		.06	4	2	6	.30		.05			
565.8	566.7	33924	.9	.9	2C0	2.88	.10	.30	.40	7.15		.02	3	2	6	.36		.04			
566.7	572.0	33925	5.3	5.3	0Q0&	2.72	.11	.83	.35	38.26		.02	1		1	.21		.02			
572.0	578.9	33926	6.9	6.5	0Q0&	2.84	.32	1.31	.48	141.52		.02	5		5	.17		.06			

DDH: 84F-20 UTM-N: 9099.0 UTM-E: 14901.6 UTM-ELEV: 3912.5 TOTAL DEPTH: 556.0 SECTION: 121+000
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
348.8	350.3	33944	1.5	1.5	2C9	2.88	.64	.30	.48	27.06		.05	4	4	8	.42		.11			
350.3	351.9	33945	1.6	1.6	2E49	3.90	.22	3.79	4.67	73.41		.04		23	24	.22		.12			
351.9	355.0	33946	3.1	2.9	2E0	4.22	.05	1.02	1.27	17.42		.07	1	29	31	.45		.01			
355.0	356.7	33947	1.7	1.7	2G02	4.55	.10	2.53	3.72	32.97		.18	2	31	33	9.96		.03			
356.7	359.1	33948	2.4	2.4	2G4	4.61	.13	6.44	8.19	90.82		.06	1	19	20	10.43		.12			
359.1	362.1	33949	3.0	3.0	2G4	4.73	.12	6.75	8.84	94.25		.09	4	18	22	15.14		.07			
362.1	367.0	33950	4.9	4.5	2E48	4.71	.17	7.22	7.97	139.03		.03	4	19	23	.50		.29			
367.0	368.2	33951	1.2	1.2	2E49	3.51	.33	4.28	.57	87.09		.05		22	22	.37		.01			
368.2	371.4	33952	3.2	3.0	2E46	4.59	.04	4.04	7.98	55.05		.03	1	33	34	2.95		.01			
371.4	375.4	33953	4.0	3.9	2D43	3.32	.09	4.14	8.40	58.48		.17		19	20	.22		.01			
375.4	379.5	33954	4.1	4.1	2D3	3.71	.07	1.29	3.08	16.80		1.37	2	26	28	.20		.12			
379.5	384.5	33955	5.0	5.0	2E4	4.78	.07	2.58	5.38	28.63		.04	1	15	17	.17		.05			
384.5	385.3	33956	.8	.8	2G1	4.62	.03	.60	.95	10.57		.07		28	29	6.32		.01			
385.3	389.3	33957	4.0	3.9	2E41	3.46	.04	1.72	3.19	28.30		.12		26	27	.18		.01			
389.3	393.0	33958	3.7	3.2	2E1	4.17	.04	.40	.64	12.75		.19	1	28	29	.17		.01			
393.0	397.0	33959	4.0	3.7	2E4	4.61	.07	5.32	7.22	85.23		.32	1	24	26	.15		.02			
397.0	399.1	33960	2.1	2.1	2E1	3.96	.16	3.78	3.72	22.71		.04	1	36	37	.21		.02			
399.1	402.3	33961	3.2	3.0	2E09	4.60	.27	1.11	.98	5.60		.04	1	37	38	.14		.03			
402.3	405.5	33962	3.2	2.0	2E09	4.71	.34	.60	3.46	3.01		.02	1	31	33	.14		.03			
405.5	407.3	33963	1.8	1.8	2C39	4.16	.29	.12	1.75	7.47		.08	1	23	24	.17		.02			
407.3	409.1	33964	1.8	1.8	2C35	3.82	.10	.59	3.29	7.78		.10	1	27	28	.18		.02			
409.1	414.0	33965	4.9	4.9	2C38	4.03	.11	.53	1.59	6.22		.07	1	27	29	.15		.02			
414.0	418.9	33966	4.9	4.9	2C38	4.18	.25	.06	1.22	11.51		.08	1	29	31	.15		.02			
418.9	423.8	33967	4.9	4.9	2C38	4.13	.08	.17	.84	4.67		.08	1	18	19	.15		.02			
423.8	424.7	33968	.9	.9	2D39	3.50	.22	.36	4.85	8.71		.11	2	16	19	.27		.05			
424.7	425.7	33969	1.0	1.0	2C3	3.71	.13	.11	2.30	4.98		.10	1	23	25	.20		.02			
425.7	426.9	33970	1.2	1.2	2C53	3.58	.04	.16	1.24	3.42		.12		23	24	.20		.02			
426.9	428.7	33971	1.8	1.2	2D43	3.77	.20	8.34	6.25	55.37		.13	2	15	17	.22		.03			
428.7	432.8	33972	4.1	4.1	2C39	4.22	.26	.58	1.46	12.13		.10	1	31	33	.14		.02			
432.8	436.9	33973	4.1	4.0	2C39	3.86	.43	.83	.46	11.51		.09	1	25	27	.15		.05			
436.9	440.9	33974	4.0	4.0	2E48	4.42	.28	2.52	4.40	9.33		.04	7	27	34	.14		.05			
440.9	444.9	33975	4.0	4.0	2E89	4.54	.35	1.07	2.21	6.22		.03	7	32	39	.15		.23			
444.9	449.0	33976	4.1	4.1	2E89	4.48	.29	.48	2.34	4.98		.02	9	31	40	.15		.29			
449.0	452.2	33977	3.2	3.2	2E19	4.19	.42	.08	1.42	4.04		.05	5	29	35	.15		.15			
452.2	455.4	33978	3.2	3.2	2C39	3.92	.80	.17	1.27	10.26		.09	1	26	27	.14		.03			
455.4	458.6	33979	3.2	3.2	2C39	3.92	.29	.67	.59	8.40		.08	1	26	28	.15		.03			
458.6	461.0	33980	2.4	2.4	2D43	3.69	.16	3.86	9.57	14.00		.09	3	17	20	.20		.04			
461.0	465.7	33981	4.7	4.7	2C3	3.80	.14	.85	2.45	5.91		.08	4	13	17	.17		.09			
465.7	470.5	33982	4.8	4.8	2C39	3.89	.44	.28	.92	7.78		.08	3	27	30	.15		.08			
470.5	472.2	33983	1.7	1.7	2E41	3.99	.35	1.22	4.91	8.71		.08	5	25	30	.16		.14			
472.2	475.9	33984	3.7	3.7	2D39	4.20	.25	1.86	5.49	9.02		.06	4	27	32	.15		.14			
475.9	480.4	33985	4.5	4.5	2C39	3.91	.32	.65	2.65	6.22		.10	4	24	28	.13		.14			
480.4	484.8	33986	4.4	4.4	2D39	4.08	.48	1.61	2.68	8.71		.06	6	26	33	.14		.23			
484.8	487.0	33987	2.2	2.1	2E41	4.33	.11	4.54	9.63	14.62		.06	4	25	29	.15		.10			
487.0	492.0	33988	5.0	5.0	2D43	3.83	.07	3.42	8.55	20.53		.12	4	17	21	.18		.05			

DDH: 84F-21 UTM-N: 9503.5 UTM-E: 15296.3 UTM-ELEV: 3908.4 TOTAL DEPTH: 397.0 SECTION: 121+000
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

-----DEPTHS----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
126.0	133.2	33927	7.2	7.0	2C37	3.15	.26	.10	.26	16.17		.03	9	7	16	.20		.05			
133.2	136.6	33928	3.4	3.4	2C37	3.34	.21	.09	.32	11.51		.03	17	7	24	.18		.04			
303.5	305.0	33929	1.5	1.5	2L12	2.90	.03	.22	.32	4.98		.04	2	2	4	.38		.06			
305.0	305.8	33930	.8	.8	2D03	3.17	.10	1.49	4.02	12.44		.08	6	3	9	.26		.04			
305.8	307.8	33931	2.0	2.0	2L14	2.81	.03	.11	.40	1.55		.10	2	2	4	.42		.05			
307.8	309.0	33932	1.2	1.2	2B7	2.82	.04	.27	.97	4.35		.06	2	2	4	.33		.06			
309.0	311.0	33933	2.0	2.0	2L14	2.94	.11	2.52	2.94	54.43		.30	5	4	9	.29		.05			
311.0	313.6	33934	2.6	2.0	2D37	3.14	.21	3.92	2.89	93.93		.53	5	3	8	.28		.05			

DDH: 84F-22 UTM-N: 9701.1 UTM-E: 15096.5 UTM-ELEV: 3752.0 TOTAL DEPTH: 185.0 SECTION: 119+000
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

-----DEPTHS-----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
47.0	48.3	33935	1.3	1.3	2C39	3.22	.22	.61	.27	46.03		1.71	8	11	19	.18		.02			
55.7	58.1	33936	2.4	2.3	2D0&	3.02	.13	1.80	4.35	33.28		.14	4	5	10	.24		.05			
70.7	75.3	33937	4.6	4.6	2D4&	3.24	.12	4.65	9.60	44.47		.23	5	5	10	.17		.03			
75.3	79.9	33938	4.6	4.6	2D4&	3.52	.09	4.10	11.48	25.51		.17	4	4	8	.17		.02			
79.9	84.6	33939	4.7	4.7	2B0&	2.70	.03	.09	.25	1.87		.02	3	1	4	.30		.13			
89.6	94.6	33940	5.0	5.0	2D0&	3.35	.13	1.71	6.95	17.73		.09	6	8	15	.18		.04			
94.6	99.6	33941	5.0	5.0	2D0&	3.12	.07	1.62	5.42	20.22		.13	3	7	11	.34		.02			
99.6	104.6	33942	5.0	5.0	2D4&	3.46	.09	2.60	8.02	31.73		.14	5	10	16	.26		.03			
104.6	109.5	33943	4.9	4.9	2D9&	3.09	.20	2.23	5.59	32.04			4	6	10	.32		.03			

DDH: 84F-23 UTM-N: 8513.0 UTM-E: 14728.7 UTM-ELEV: 3909.7 TOTAL DEPTH: 572.0 SECTION: 123+000
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 210 DHD CALC: 1 SS CALC: 1

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	---ASSAYS---														
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
302.7	304.1	33989	1.4	1.4	2B0	2.84	.08	.18	2.93	3.42		.01	6	3	9	.61		.06			
304.1	308.0	33990	3.9	3.9	2C37	3.44	.32	.12	3.05	5.91		.32	11	19	30	.18		.04			
308.0	311.8	33991	3.8	3.4	2D43	3.49	.31	.25	9.97	10.58		.39	6	15	22	.17		.04			
311.8	314.1	33992	2.3	2.3	2E1&	3.76	.13	.20	1.20	7.78		.14	5	22	27	.15		.06			
314.1	315.3	33993	1.2	1.2	2D43	3.40	.09	2.50	8.24	27.37		.25	3	13	16	.20		.08			
315.3	318.1	33994	2.8	2.8	2E0	4.70	.07	.44	.70	6.53		.04	1	35	36	.18		.03			
318.1	322.3	33995	4.2	4.2	2E41	4.73	.07	3.26	7.16	41.06		.22	2	28	30	6.51		.09			
322.3	325.2	33996	2.9	2.9	2L14	3.36	.15	1.85	3.21	39.19		.20	4	8	12	9.62		.27			
325.2	328.8	33997	3.6	3.6	2G41	4.53	.11	6.30	6.40	139.66		.65	7	15	23	13.82		.44			
328.8	334.5	33998	5.7	5.7	2L1	3.01	.11	.81	.48	13.06		.09	2	2	5	9.53		.07			
334.5	336.2	33999	1.7	1.7	2H49	4.04	.23	6.46	8.17	122.24		.21	16	10	26	3.46		.63			
336.2	341.3	34000	5.1	5.1	2L4	3.32	.17	1.46	1.50	36.70		.08	8	8	16	6.30		.19			
341.3	344.0	34901	2.7	2.7	2B06	2.86	.04	.74	1.06	15.55		.02	2	2	5	4.51		.07			
344.0	346.3	34902	2.3	2.3	0Q0	2.92	.02	.42	1.10	7.15		.02	1		1	2.35		.07			
346.3	348.1	34903	1.8	1.8	2B06	3.05	.06	.40	.46	9.33		.08	2	2	5	12.11		.03			
348.1	353.6	34904	5.5	5.5	1H41	2.76	.05	.15	.12	4.98		.02	4	2	6	2.15		.07			
353.6	357.5	34905	3.9	3.9	2L1	3.03	.05	.28	.66	6.84		.01	3	1	4	6.75		.04			
357.5	359.5	34906	2.0	2.0	2L1*	3.28	.07	.12	.30	8.39		.02	3	2	5	25.16		.05			
359.5	366.5	34907	7.0	6.8	2L1	2.99	.04	.44	.46	10.26		.02	4	2	7	4.66		.13			
366.5	370.8	34908	4.3	4.2	1E19	2.79	.02	.20	.22	4.04		.02	2	1	3	3.55		.05			
370.8	372.2	34909	1.4	1.4	2L14	2.97	.04	.85	1.44	18.66		.40	3	2	6	3.52		.11			
372.2	373.9	34910	1.7	1.7	1E&9	2.79	.04	.50	.61	10.89		.02	2	1	4	3.83		.07			
373.9	378.8	34911	4.9	4.9	2D0&	3.21	.10	3.17	3.24	74.65		.04	9	3	13	3.57		.21			
378.8	384.1	34912	5.3	5.3	2E47	4.89	.24	3.19	4.74	64.07		.03	14	15	29	.78		.22			
384.1	390.7	34913	6.6	6.6	2L14	3.06	.11	.43	.49	13.37			4	5	9	3.79		.05			
390.7	394.4	34914	3.7	3.7	1H4*	3.30	.10	1.25	1.42	31.10		.02	5	5	10	10.72		.07			
394.4	398.3	34915	3.9	3.9	2K46	3.61	.28	3.00	7.03	46.66		.04	22	5	27	11.15		.13			
398.3	402.6	34916	4.3	4.3	2H49	4.36	.51	4.54	8.00	48.83		.03	34	18	52	.59		.15			
402.6	407.4	34917	4.8	4.8	2H09	4.50	.66	3.27	5.15	42.92		.03	42	28	70	.22		.11			
407.4	413.2	34918	5.8	5.8	2E46	4.55	.37	3.76	6.08	47.59		.05	15	27	42	1.33		.10			
413.2	418.2	34919	5.0	5.0	2G49	4.76	.20	.59	7.07	49.77		.03	4	24	28	9.76		.06			
418.2	423.2	34920	5.0	5.0	2G4	4.56	.12	3.62	6.30	44.17		.03	2	20	22	20.62		.07			
423.2	429.6	34921	6.4	3.4	2G4	4.47	.13	4.91	9.06	53.19		.02	2	14	17	29.83		.08			
429.6	434.8	34922	5.2	5.0	2E49	4.76	.45	2.56	4.25	37.64		.20	3	39	43	.68		.10			
434.8	441.0	34923	6.2	6.2	2F4I	4.81	.07	8.09	13.76	60.96		.20	2	29	31	.17		.02			
441.0	444.7	34924	3.7	3.7	2E4	4.78	.19	4.89	8.94	41.99		.02	1	35	37	.15		.03			
444.7	446.2	34925	1.5	1.5	2E48	4.78	.56	4.03	5.09	39.19		.01	6	36	42	.18		.18			
446.2	451.8	34926	5.6	5.6	2E49	4.77	.50	4.84	4.80	46.66		.03	4	36	40	.17		.12			
451.8	457.8	34927	6.0	6.0	2E48	4.83	.33	1.97	2.46	30.17		.03	5	40	46	.31		.16			
457.8	462.7	34928	4.9	4.9	2G4	4.63	.14	6.68	8.16	72.47		.04	2	21	24	15.02		.17			
462.7	467.1	34929	4.4	4.4	2G4	4.66	.11	5.07	6.60	68.11		.04	3	19	23	18.74		.17			
467.1	469.0	34930	1.9	1.9	2E49	4.89	.39	4.42	3.95	49.46		.12	4	34	39	.70		.14			
469.0	470.8	34931	1.8	1.8	2E89	4.66	.49	1.47	2.20	29.86		.20	6	10	17	.34		.18			
470.8	475.8	34932	5.0	5.0	2F4	4.71	.07	5.17	10.70	39.50		.02	2	31	33	.16		.02			
475.8	481.3	34933	5.5	5.5	2F49	4.71	.20	4.95	11.09	37.64		.02	3	33	36	.15		.09			
481.3	487.2	34934	5.9	5.9	2F09	4.90	.28	2.67	5.12	29.24		.02	2	39	41	.15		.05			
487.2	488.8	34935	1.6	1.6	2E47	4.41	.46	2.38	3.57	38.26		.04	18	25	43	.23		.13			
488.8	491.7	34936	2.9	2.8	2E48	4.69	.36	2.72	4.50	32.04		.08	5	35	40	.14		.10			
491.7	494.0	34937	2.3	2.3	2D39	3.75	.38	4.26	5.89	40.75		.07	9	16	25	.18		.09			
494.0	497.0	34938	3.0	3.0	2D09	3.20	.20	2.70	3.45	37.01		.05	7	10	18	.36		.13			
497.0	502.0	34939	5.0	5.0	2A4	2.85	.07	2.53	6.27	44.48		1.82	2	4	7	.27		.03			

DDH: 84F-23 UTM-N: 8513.0 UTM-E: 14728.7 UTM-ELEV: 3909.7 TOTAL DEPTH: 572.0 SECTION: 123+000
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 210 DHD CALC: 1 SS CALC: 1

-----DEPTHS-----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
502.0	507.2	34940	5.2	5.2	2A4	2.80	.06	2.25	3.41	36.39		.47	2	4	6	.28		.02			
507.2	510.7	34941	3.5	3.5	2A0	2.73	.04	.53	1.19	20.53		.05	2	3	5	.54		.02			
510.7	514.4	34942	3.7	3.7	2A0	2.69	.05	.69	2.30	23.95		.02	1	3	5	.48		.02			
514.4	518.5	34943	4.1	4.1	2B0	2.84	.07	.21	3.19	22.08		.10	1	3	4	.34		.04			
518.5	520.5	34944	2.0	2.0	2A0	2.80	.09	.68	.97	23.02		.10	1	4	5	.35		.01			
520.5	525.0	34945	4.5	4.5	2B09	2.94	.50	.24	.85	28.30		.18	3	6	9	.35		.03			

DDH: 84F-24 UTM-N: 8082.8 UTM-E: 14307.2 UTM-ELEV: 3910.1 TOTAL DEPTH: 545.0 SECTION: 123+000
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

-----DEPTHS-----		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
435.5	439.0	34946	3.5	3.5	2A0	2.85	.05	.66	.48	14.00		.12		8	8	.33		.01			
439.0	442.5	34947	3.5	3.3	2A0	2.94	.12	1.13	.36	21.77		.20		10	11	.36		.01			
442.5	443.6	34948	1.1	1.1	2C5	3.22	.17	.18	.20	13.37		.19	1	12	14	.35		.02			
443.6	446.3	34949	2.7	2.7	2A0	2.84	.08	.92	.88	11.51		.04	2	3	5	.61		.04			
446.3	449.1	34950	2.8	2.5	2A4	2.79	.04	1.69	3.14	18.98		.08	2		3	.43		.05			
449.1	451.8	34951	2.7	2.7	2E41	3.89	.20	4.76	8.87	74.34		.07	11	14	26	.21		.11			
451.8	455.1	34952	3.3	3.3	2D0	3.02	.08	.76	4.03	15.86		.10	4	3	8	.44		.04			
455.1	458.4	34953	3.3	3.3	2D0	2.94	.05	.54	4.12	11.82		.02	3	2	5	.50		.03			
458.4	459.3	34954	.9	.9	2A0	2.96	.07	.49	2.06	9.95		.03	3	2	5	.38		.02			
459.3	460.3	34955	1.0	1.0	2D5	3.06	.11	1.31	3.56	14.93		.03	3	3	7	.34		.02			
460.3	463.0	34956	2.7	2.7	2A0	2.86	.07	.50	2.81	13.37		.16	4	2	6	.43		.04			
463.0	466.9	34957	3.9	3.9	2D0	3.06	.16	.73	4.35	25.51		.19	5	5	10	.43		.04			
466.9	468.1	34958	1.2	1.2	2D5	2.92	.07	.57	3.06	14.00		.21	5	2	7	.42		.04			
468.1	470.3	34959	2.2	2.2	2A0	2.82	.06	.20	1.07	10.89		.03	3	2	5	.47		.02			
470.3	471.6	34960	1.3	1.3	2B0&	3.00	.05	.11	.49	6.22		.04	3	2	5	.49		.03			
471.6	472.6	34961	1.0	1.0	2A0	2.91	.05	.34	1.49	10.58		.13	2	1	3	.41		.02			
472.6	473.9	34962	1.3	1.3	2B0	2.89	.06	.09	.55	7.46		.02	3	2	5	.42		.03			
473.9	477.6	34963	3.7	3.7	2A0	2.90	.07	.18	.53	6.22		.02	3	2	6	.43		.02			
477.6	481.3	34964	3.7	3.7	2B0&	2.86	.04	.71	2.23	11.82		.03	2	1	3	.36		.02			
481.3	485.0	34965	3.7	3.7	2B4&	3.03	.07	1.19	2.91	20.22		.02	3	2	6	.35		.02			
485.0	488.1	34966	3.1	3.1	2D0	3.03	.08	1.44	5.20	34.52		.05	6	2	8	.34		.03			
488.1	491.2	34967	3.1	3.1	2D0	3.01	.10	1.47	3.96	46.03		.15	4	3	8	.37		.03			
491.2	491.8	34968	.6	.6	2C5	3.03	.07	.79	3.14	23.95		.10	4	6	10	.27		.02			
491.8	495.2	34969	3.4	3.3	2A0	2.78	.08	.26	1.43	14.00		.05	3	2	5	.35		.04			
495.2	498.5	34970	3.3	3.3	2A0	2.84	.07	.61	1.20	11.82		.06	3	5	8	.37		.03			

DDH: 84F-25 UTM-N: 8690.0 UTM-E: 14912.0 UTM-ELEV: 3911.0 TOTAL DEPTH: 591.0 SECTION: 123+015
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

-----DEPTHS-----						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
281.5	282.6	35023	1.1	1.1	1E19	2.87	.12	.06	.17	2.80		.04	5	1	6	.30		.05			
282.6	283.9	35024	1.3	1.3	2C09	3.12	.24	.05	.10	5.29		.02	8	6	14	.18		.05			
283.9	287.9	35025	4.0	3.2	2C37	3.45	.41	.04	.12	5.29		.03	14	17	32	.15		.08			
287.9	291.9	35026	4.0	4.0	2C37	3.48	.48	.01	.36	2.18		.04	22	4	26	.16		.08			
291.9	296.9	35027	5.0	5.0	2C3*	3.57	.19	.04	.43	3.42		.09	5	8	14	.17		.08			
296.9	303.3	35028	6.4	6.4	2C3*	3.34	.31	.09	.40	4.04		.03	9	14	23	.16		.10			
303.3	304.6	35029	1.3	1.3	2A0	2.87	.11	.06	.09	.93		.02	5	3	8	.52		.10			
349.2	350.8	35030	1.6	1.6	2D09	3.39	.24	2.14	2.62	43.55		.28	6	12	18	.35		.08			
350.8	355.2	35031	4.4	4.4	2G4	4.73	.05	5.04	7.15	105.75		.34	2	18	21	18.91		.10			
355.2	356.4	35032	1.2	1.2	1H4	3.10	.37	1.88	2.98	54.74		.32	5	12	17	5.16		.22			
356.4	358.2	35033	1.8	1.8	2E4	4.54	.06	2.56	4.58	57.23		.14	4	31	36	.84		.12			
358.2	360.7	35034	2.5	2.5	2L4	2.91	.07	.27	.45	4.67		.02	2	4	7	4.41		.10			
360.7	364.8	35035	4.1	4.1	2E4&	4.36	.05	3.86	5.76	84.91		.12	6	24	31	2.05		.13			
364.8	366.9	35036	2.1	2.1	10E44	3.02	.05	.42	.40	6.53		.02	3	2	6	9.38		.10			
366.9	371.2	35037	4.3	4.3	2E1&	4.52	.05	2.90	2.92	54.43		.16	3	31	35	2.23		.22			
371.2	375.5	35038	4.3	4.3	2G4	4.36	.13	5.23	9.50	87.09		.19	7	4	12	26.40		.10			
375.5	381.4	35039	5.9	5.9	2E&8	4.50	.20	1.31	1.37	37.64		.10	8	31	40	.49		.21			
386.0	387.6	35040	1.6	1.6	2E13	3.57	.28	1.05	1.55	32.97		.33	2	22	25	3.04		.21			
393.8	399.7	35041	5.9	5.9	2E0&	4.66	.17	1.07	.69	21.78		.17	3	36	39	.26		.06			
399.7	405.8	35042	6.1	6.1	2E41	4.67	.06	2.19	1.88	24.58		.10	1	30	32	.22		.03			
405.8	410.0	35043	4.2	3.7	2C3	3.71	.06	.78	.33	32.97		2.19		19	19	.16		.02			
410.0	415.0	35044	5.0	5.0	2C3	3.44	.03	.40	.14	12.44		.60		18	19	.17		.01			
415.0	419.5	35045	4.5	4.5	2E1	4.53	.06	1.04	1.42	15.24		.15	1	35	36	.14		1.00			
419.5	420.9	35046	1.4	1.4	2E89	4.65	.41	1.88	1.67	24.26		.18	6	34	40	.17		.25			
420.9	423.0	35047	2.1	2.1	2E19	4.69	.23	1.86	2.90	20.84		.06		34	34	.14		.05			
423.0	428.0	35048	5.0	5.0	2F49	4.55	.33	4.82	6.84	50.08		.10	2	29	31	.89		.04			
428.0	433.3	35049	5.3	3.7	2F49	4.90	.33	5.04	7.30	71.85		.10	4	26	30	3.95		.20			
433.3	435.2	35050	1.9	1.9	2G4	4.52	.12	2.74	7.57	45.72		.05	2	17	19	23.33		.08			
435.2	437.5	35051	2.3	2.3	2E4	4.83	.07	2.18	5.17	23.33		.07	1	34	35	.65		.03			
437.5	441.2	35052	3.7	3.7	2E41	4.18	.24	2.09	2.52	37.64		.08	4	25	29	.28		.20			
441.2	443.8	35053	2.6	2.3	2E4	4.75	.14	4.63	8.25	56.61		.10	2	30	32	.17		.10			
443.8	448.8	35054	5.0	5.0	2E09	4.66	.27	3.30	2.53	38.57		.06	3	30	34	.15		.13			
448.8	453.8	35055	5.0	5.0	2E49	4.78	.35	2.25	3.04	35.15		.11	3	31	34	.15		.07			
453.8	458.7	35056	4.9	4.9	2E49	4.68	.21	3.32	2.13	8.88		.05	2	31	33	.16		.04			
458.7	464.5	35057	5.8	5.8	2E1	4.31	.14	1.31	.60	21.15		.05	1	31	33	.15		.21			
464.5	468.5	35058	4.0	4.0	2E41	4.43	.26	2.81	6.06	32.97		.06	5	26	31	.15		.06			
468.5	473.0	35059	4.5	4.3	2E41	4.52	.17	2.18	2.54	23.02		.06	2	31	33	.17		.38			
473.0	478.0	35060	5.0	5.0	2E48	4.49	.33	2.05	3.42	19.59		.05	9	25	34	.15		.28			
478.0	483.0	35061	5.0	5.0	2E48	4.47	.26	2.44	3.83	19.28		.04	7	27	34	.13		.15			
483.0	488.0	35062	5.0	5.0	2E48	4.18	.42	2.03	2.18	16.17		.06	5	25	31	.15		.18			
488.0	491.4	35063	3.4	3.4	2E48	4.53	.29	2.51	4.02	10.57		.03	6	25	32	.16		.03			
491.4	494.4	35064	3.0	3.0	2E4	4.99	.08	3.53	7.42	18.35		.04	2	32	34	.14		.04			
494.4	498.2	35065	3.8	3.8	2E4	4.88	.09	2.26	4.60	14.00		.05	2	32	34	.15		.04			
498.2	500.1	35066	1.9	1.9	2E4	4.86	.08	4.04	7.90	22.39		.04	2	32	35	.31		.05			
500.1	501.7	35067	1.6	1.6	2G41	3.57	.32	6.54	12.23	53.50		.07	7	8	16	.28		.04			
501.7	503.5	35068	1.8	1.8	2C09	3.06	.21	1.72	2.07	25.19		.03	6	5	12	.27		.04			
503.5	504.5	35069	1.0	1.0	1D4	2.91	.09	.32	1.31	3.73		.02	3	1	5	.52		.05			
504.5	505.8	35070	1.3	1.3	2C9	3.09	.20	1.16	1.62	15.86		.05	5		6	.38		.06			

DDH: 84F-25 UTM-N: 8690.0 UTM-E: 14912.0 UTM-ELEV: 3911.0 TOTAL DEPTH: 591.0 SECTION: 123+015
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

-----DEPTHS---							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
505.8	506.6	35071	.8	.8	1H4	3.36	.32	.10	1.95	4.98		.04	8	11	20	.62		.07			
506.6	512.0	35072	5.4	5.3	2C59	3.14	.25	.25	.60	5.59		.04	5	6	12	.33		.03			
512.0	518.5	35073	6.5	6.5	2A0	2.80	.06	.35	.93	9.02		.03	2	1	3	.35		.03			
537.0	542.9	35074	5.9	5.9	0Q0&	3.01	.07	3.04	.46	57.85		.06	1		1	.14		.03			

DDH: 84F-26 UTM-N: 8986.0 UTM-E: 15204.3 UTM-ELEV: 3912.2 TOTAL DEPTH: 504.0 SECTION: 123+015
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	ASSAYS														
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
224.7	225.2	34971	.5	.5	2E47	3.48	.11	.70	12.27	51.01		.04	15		15	2.14		.08			
270.3	271.2	34972	.9	.9	2D39	3.81	.70	1.83	4.27	45.41		.23	8	14	23	.44		.08			
271.2	273.4	34973	2.2	.8	2G4	4.66	.05	3.77	7.69	51.01		.06	1	16	18	21.87		.02			
273.4	273.9	90002	.5	.0	FUDGE	2.75															
273.9	275.1	34974	1.2	1.2	2D4	3.93	.19	4.97	7.47	83.04		.82	2	13	16	.63		.08			
292.2	293.5	34975	1.3	.7	2C39	3.65	.21	.51	1.50	11.82		.33	5	16	21	.23		.06			
293.5	294.9	34976	1.4	1.4	2D4	4.29	.15	5.85	15.96	44.48		.35	8	6	15	.31		.29			
294.9	299.2	34977	4.3	4.3	2D4	3.51	.07	2.75	9.64	21.46		.34	4	7	11	.48		.10			
299.2	299.6	90003	.4	.0	FUDGE	2.75															
299.6	300.6	34978	1.0	1.0	2D09	3.35	.56	3.57	4.78	127.22		10.55	3	10	14	.27		.10			
300.6	301.7	34979	1.1	1.1	2D39	3.56	.40	2.33	2.15	129.70		2.67	7	13	20	.23		.09			
301.7	303.2	34980	1.5	1.5	2C39	3.35	.30	1.51	1.36	45.41		.28	10	9	19	.17		.13			
303.2	305.7	34981	2.5	2.5	2D4&	3.40	.12	5.75	15.40	45.41		.39	2	9	12	.22		.05			
305.7	306.2	34982	.5	.5	2D0&	3.12	.10	2.08	5.13	19.60		.07	3	9	12	.33		.10			
332.8	333.9	34983	1.1	1.1	2C39	3.69	.91	.40	3.07	27.06		.08	12	5	17	.15		.08			
333.9	335.4	34984	1.5	1.5	2E17	3.92	.33	.43	1.47	9.64		.02	32	1	33	.15		.08			
335.4	340.4	34985	5.0	5.0	2C39	4.14	.24	.47	1.44	9.64		.06	6	19	25	.15		.08			
340.4	345.4	34986	5.0	5.0	2C39	3.84	.36	.16	.89	5.29		.08	12	17	29	.15		.08			
345.4	350.4	34987	5.0	5.0	2C3&	3.71	.12	1.72	2.18	15.87		.11	7	16	24	.20		.04			
350.4	355.4	34988	5.0	5.0	2C39	3.53	.34	1.51	2.87	20.22		.21	6	12	18	.24		.05			
355.4	358.4	34989	3.0	3.0	2C39	3.24	.64	1.31	.32	33.90		.30	11	7	19	.20		.03			
358.4	360.5	34990	2.1	2.1	2C39	3.27	.19	.14	.31	6.84		.04	10	9	20	.21		.08			
365.0	368.0	34991	3.0	3.0	2D09	3.26	.46	1.60	3.10	27.06		.93	5	10	16	.26		.08			
368.0	370.5	34992	2.5	2.5	2D3	3.51	.11	1.31	3.92	13.37		.26	2	16	18	.22		.03			
370.5	375.2	34993	4.7	4.7	2C0&	3.26	.06	.37	1.34	7.46		.20	2	14	16	.26		.02			
375.2	378.2	34994	3.0	3.0	2C3	3.48	.09	.70	2.62	12.13		.19	2	15	17	.18		.02			
378.2	381.6	34995	3.4	3.4	2C39	3.51	.22	2.25	1.09	16.49		.16	2	15	17	.21		.02			
381.6	384.7	34996	3.1	3.1	2C3&	3.65	.11	.19	.41	7.46		.22	1	18	20	.22		.01			
384.7	388.1	34997	3.4	3.4	2C39	3.70	.34	.07	.47	1.56		.10	1	26	28	.16		.01			
388.1	391.5	34998	3.4	3.4	2C39	3.89	.22	.06	.88	6.53		.10	1	22	24	.18		.02			
391.5	394.9	34999	3.4	3.4	2C3	3.76	.25	.08	.37	6.00		.11	2	22	24	.18		.02			
394.9	396.1	35000	1.2	1.2	2A39	3.49	.21	.11	.61	1.87		.12	2	16	19	.22		.03			
396.1	399.5	35001	3.4	3.4	2C3	4.03	.07	.05	2.15	4.04		.08	2	24	26	.16		.02			
399.5	402.9	35002	3.4	3.4	2C3	3.87	.09	.06	1.22	2.49		.08	1	24	26	.17		.03			
402.9	406.3	35003	3.4	3.4	2C3&	3.84	.18	.48	2.79	3.11		.08	2	21	23	.18		.08			
406.3	409.8	35004	3.5	3.5	2C39	4.00	.34	.44	1.83	4.04		.05	4	22	27	.15		.24			
409.8	413.3	35005	3.5	3.5	2E89	4.04	.88	.12	1.32	6.84		.05	9	8	17	.13		.24			
413.3	416.8	35006	3.5	3.5	2E89	4.23	.27	.32	1.40	5.29		.10	8	25	34	.14		.16			
416.8	418.4	35007	1.6	1.6	2C39	3.65	.37	.05	.57	1.24		.05	7	14	21	.15		.24			
418.4	420.7	35008	2.3	2.3	2E89	4.55	.45	.04	1.58	3.73		.06	9	26	35	.14		.14			
420.7	423.7	35009	3.0	3.0	2C39	3.78	.48	.47	.94	4.98		.10	6	19	25	.14		.06			
423.7	426.4	35010	2.7	2.7	2C39	3.73	.46	.52	.99	5.60		.07	3	17	21	.14		.17			
426.4	428.3	35011	1.9	1.9	2C38	4.37	.33	1.37	.87	8.40		.10	6	22	29	.14		.12			
428.3	432.0	35012	3.7	3.7	2C3	3.71	.08	.66	1.62	6.53		.11	6	17	24	.14		.03			
432.0	433.8	35013	1.8	1.8	2D43	3.83	.06	5.67	7.48	12.75		.10	3	16	20	.16		.02			
433.8	437.7	35014	3.9	3.9	2C3	3.66	.06	.24	1.20	1.87		.12	2	19	21	.16		.02			
437.7	438.5	35015	.8	.8	2D3	3.64	.06	.37	6.01	2.80		.12	4	16	20	.20		.03			

DDH: 84F-26 UTM-N: 8986.0 UTM-E: 15204.3 UTM-ELEV: 3912.2 TOTAL DEPTH: 504.0 SECTION: 123+015
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

-----DEPTHS-----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
438.5	441.9	35016	3.4	3.4	2D3	3.74	.05	1.53	4.15	8.71		.12	2	18	20	.17		.02			
441.9	443.7	35017	1.8	1.7	2E4	4.63	.03	5.15	9.75	36.39		.10	2	29	31	.17		.02			
443.7	444.4	35018	.7	.7	2D4	3.52	.06	1.12	10.57	14.93		.14	5	12	17	.22		.04			
444.4	445.2	35019	.8	.8	2E0	4.73	.07	.41	1.86	5.91		.06	2	36	38	.13		.02			
445.2	445.7	35020	.5	.5	2E4	4.78	.04	1.76	8.19	16.49		.07	6	28	35	.13		.06			
445.7	446.4	35021	.7	.7	2D35	3.35	.11	1.75	3.22	26.12		.16	4	14	19	.26		.03			
446.4	449.0	35022	2.6	2.6	2D0	3.21	.15	2.18	7.13	27.68		.15	5	4	9	.30		.05			

DDH: 84F-27 UTM-N: 9188.5 UTM-E: 15400.9 UTM-ELEV: 3914.4 TOTAL DEPTH: 355.0 SECTION: 123+015
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 0 DHD CALC: 1 SS CALC: 1

-----DEPTHS----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
238.7	240.7	35075	2.0	2.0	2C7	3.22	.09	.42	.41	11.20		.05	15		16	.58		.02			
240.7	243.3	35076	2.6	2.6	2C35	3.25	.11	.05	2.22	4.35		.12	22	1	23	.28		.02			
288.1	288.8	35077	.7	.7	2D7	3.01	.07	.74	5.85	6.53		.12	7		8	.24		.04			
316.5	318.0	35078	1.5	1.4	2C57	3.03	.11	.26	.74	6.22		.04	9	3	13	.43		.03			
318.0	318.7	35079	.7	.5	2H41	3.76	.11	1.57	20.21	23.02		.03	22	2	25	.15		.05			
322.6	325.3	35080	2.7	2.7	2C79	3.44	.24	.16	.36	5.91		.14	34	2	36	.17		.02			
325.3	326.5	35081	1.2	1.1	2C57	3.20	.29	.09	.81	3.42		.03	18		19	.21		.03			

DDH: 86F-01 UTM-N: 9500.0 UTM-E: 14750.0 UTM-ELEV: 3726.0 TOTAL DEPTH: 209.0 SECTION: 118+070
RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 315 DHD CALC: 1 SS CALC: 1

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
50.0	52.0	34651	2.0	2.0	2D43	3.81	.09	6.10	12.90	61.00											
52.0	57.5	34652	5.5	5.5	2E41	4.83	.16	1.80	2.99	16.00											
57.5	61.5	34653	4.0	4.0	2E0	5.01	.25	.05	.07	6.00											
61.5	66.7	34654	5.2	5.2	2E0	4.74	.21	.34	.37	11.00											
66.7	75.4	34655	8.7	6.7	2C3BX	4.24	.15	1.65	1.75	15.00											
75.4	78.7	34656	3.3	3.3	2E84	4.74	.16	2.69	3.59	11.00											
78.7	84.1	34657	5.4	5.4	2E84	4.79	.16	3.25	3.24	12.00											
84.1	89.0	34658	4.9	4.9	2E80	4.67	.18	.76	1.50	6.00											
89.0	94.3	34659	5.3	5.3	2E84	3.64	.20	4.18	6.28	22.00											
94.3	100.7	34660	6.4	6.4	2D3	4.22	.08	3.49	7.03	26.00											
100.7	107.2	34661	6.5	6.5	2D0&5	3.73	.06	2.60	6.30	20.00											
107.2	110.5	34662	3.3	3.3	2A4	3.53	.09	5.34	4.25	99.00											
110.5	116.0	34663	5.5	5.5	2D35	4.19	.10	3.03	5.83	25.00											
116.0	122.1	34664	6.1	6.1	2E418	4.59	.14	3.35	5.71	6.00											
122.1	127.3	34665	5.2	5.2	2C38	3.90	.19	.22	2.61	5.00											
127.3	132.8	34666	5.5	5.5	2C38	3.83	.24	.25	1.10	5.00											
132.8	137.7	34667	4.9	4.9	2C38	3.80	.29	.21	1.69	4.00											
137.7	141.3	34668	3.6	3.6	2E80	4.70	.26	.17	1.36	4.00											
141.3	146.4	34669	5.1	5.1	2C38	4.22	.45	.65	1.32	11.00											
146.4	151.0	34670	4.6	4.6	2C3	3.68	.48	.31	1.45	12.00											
151.0	157.0	34671	6.0	6.0	2C38	4.18	.44	.15	1.90	5.00											
157.0	162.5	34672	5.5	5.5	2C38	4.26	.53	.34	1.61	11.00											
162.5	166.5	34673	4.0	4.0	2C38	4.46	.23	.07	1.38	6.00											
166.5	170.8	34674	4.3	4.3	2E18	4.26	.31	.15	1.77	5.00											
170.8	175.5	34675	4.7	4.7	2E81	4.31	.18	.23	1.89	4.00											
175.5	180.0	34676	4.5	4.5	2E48	4.47	.12	3.03	7.12	5.00											
180.0	185.8	34677	5.8	5.8	2E14	4.60	.08	2.13	5.38	6.00											
185.8	191.0	34678	5.2	5.2	2E14	4.35	.05	5.40	14.30	13.00											
191.0	193.5	34679	2.5	2.5	2A4	4.11	.04	3.06	9.47	12.00											
193.5	197.5	34680	4.0	4.0	2D34	4.06	.04	2.76	8.72	13.00											
197.5	202.5	34681	5.0	5.0	2D4	3.89	.04	3.97	10.50	19.00											
202.5	206.0	34682	3.5	3.5	2E4	4.37	.02	3.58	7.10	18.00											
206.0	209.0	34683	3.0	3.0	2A4	3.53	.01	1.21	5.07	8.00											

PAGE : 260

DDH: 86F-02 UTM-N: 7652.0 UTM-E: 15482.0 UTM-ELEV: 3876.0 TOTAL DEPTH: 160.0 SECTION: 131+022
RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 315 DHD CALC: 1 SS CALC: 1

-----DEPTHS-----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
26.8	31.0	34684	4.2	4.2	2C0	3.35	.11	1.74	2.76	15.00											
51.0	52.2	34685	1.2	1.2	2H14	4.18	.12	6.66	6.11	102.00											
52.2	58.8	34686	6.6	6.6	2B0	3.04	.04	.83	1.47	16.00											
58.8	61.0	34687	2.2	2.2	2H124	4.27	.16	4.24	7.46	56.00											
61.0	64.5	34688	3.5	3.5	2E4	4.89	.02	1.54	5.23	18.00											
64.5	69.0	34689	4.5	4.5	2E0	5.00	.01	.78	2.02	13.00											
69.0	73.2	34690	4.2	4.2	2E4	4.98	.02	2.29	4.44	25.00											
73.2	80.0	34691	6.8	6.8	2H428	4.53	.26	2.81	5.78	36.00											
80.0	84.0	34692	4.0	4.0	2B7	3.07	.07	3.87	2.63	42.00											
84.0	87.7	34693	3.7	3.7	2H42	4.59	.26	3.03	5.38	29.00											
87.7	91.8	34694	4.1	4.1	2E4	5.46	.12	1.85	4.17	11.00											
91.8	96.3	34695	4.5	4.5	2E0	4.88	.26	.47	1.10	6.00											
96.3	100.8	34696	4.5	4.5	2E4	4.66	.05	2.86	4.40	12.00											
100.8	105.6	34697	4.8	4.8	2E47	4.70	.12	2.81	5.76	18.00											
105.6	109.0	34698	3.4	3.4	2D7	4.07	.15	1.60	4.23	18.00											
109.0	114.3	34699	5.3	5.3	2D75	3.12	.08	1.21	4.63	16.00											
114.3	120.5	34601	6.2	6.2	2D75	3.44	.15	1.24	4.27	47.00											
120.5	127.0	34602	6.5	6.5	2D75	3.08	.04	3.02	5.00	54.00											
127.0	132.6	34603	5.6	5.6	2D75	3.22	.08	1.94	4.38	38.00											
132.6	137.0	34604	4.4	4.4	2A0	3.13	.05	1.56	3.37	33.00											
137.0	141.5	34605	4.5	4.5	2A4	2.93	.05	1.59	3.95	26.00											
141.5	146.0	34606	4.5	4.5	2A4	2.90	.06	2.22	4.89	35.00											
146.0	150.7	34607	4.7	4.7	2A0	2.82	.04	1.21	2.86	22.00											
150.7	155.5	34608	4.8	4.8	2A0	2.90	.06	.56	.69	12.00											
155.5	160.0	34609	4.5	4.5	2A0	2.93	.10	1.30	1.27	21.00											

PAGE : 261

DDH: 86F-03 UTM-N: 7650.0 UTM-E: 15350.0 UTM-ELEV: 3874.5 TOTAL DEPTH: 161.0 SECTION: 130+000
RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 315 DHD CALC: 1 SS CALC: 1

[illegible]

!THE IMPERIAL ANVIL!

ASSAY LISTING (DEPTH SEQUENCE) DH015

PAGE : 262

DDH: 86F-04 UTM-N: 6610.0 UTM-E: 15225.0 UTM-ELEV: 4014.0 TOTAL DEPTH: 135.0 SECTION:
RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 315 DHD CALC: 1 SS CALC: 1

[illegible]

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
3.5	10.0	34731	6.5	6.5	2C35	3.44	.12	.65	1.46	11.00											
10.0	15.5	34732	5.5	5.5	2D34	3.44	.14	2.47	6.47	13.00											
15.5	19.5	34733	4.0	4.0	1D4	2.80	.06	.11	.08	6.00											
19.5	23.2	34734	3.7	3.7	2C3	3.40	.10	.60	.86	7.00											
24.2	28.0	34735	3.8	3.8	2C3	3.88	.10	1.16	1.22	13.00											
28.0	32.5	34736	4.5	4.5	1D4BX	3.22	.11	1.07	1.10	16.00											
32.5	39.2	34737	6.7	6.7	2D3	3.64	.14	1.89	3.41	17.00											
39.2	46.2	34738	7.0	7.0	2D3	3.68	.19	2.69	3.85	25.00											
46.2	50.0	34739	3.8	3.8	2C3	4.14	.30	.73	.45	10.00											
50.0	54.5	34740	4.5	4.5	2C3	4.26	.41	.70	.46	5.00											
54.5	58.5	34741	4.0	4.0	2D34	3.77	.42	4.23	6.21	37.00											
58.5	70.4	34742	11.9	11.9	1D4	2.88	.03	.10	.10	4.00											
70.4	75.5	34743	5.1	5.1	2C3	3.22	.21	1.24	1.27	20.00											
75.5	81.0	34744	5.5	5.5	2A34	3.78	.04	1.53	4.40	16.00											
81.0	87.0	34745	6.0	6.0	2A4	3.40	.06	4.40	9.94	25.00											
87.0	94.0	34746	7.0	7.0	2A4	3.43	.05	5.46	13.20	38.00											
94.0	101.0	34747	7.0	7.0	2A4	3.51	.07	6.46	7.12	107.00											
101.0	108.0	34748	7.0	7.0	2A4	3.38	.05	3.82	6.57	29.00											
108.0	114.0	34749	6.0	6.0	2A4	3.60	.04	2.56	6.64	23.00											
114.0	120.0	34750	6.0	6.0	2A4	3.24	.06	2.43	6.09	18.00											
120.0	125.0	35151	5.0	5.0	2C0	3.25	.06	.69	1.46	6.00											
125.0	131.0	35152	6.0	6.0	2D0	3.65	.08	1.87	6.61	15.00											
131.0	137.0	35153	6.0	6.0	2C0	3.17	.05	1.10	1.42	12.00											
137.0	143.0	35154	6.0	5.5	2C0	3.16	.07	.73	1.32	9.00											
143.0	149.0	35155	6.0	6.0	2D0	3.26	.08	1.07	3.80	12.00											
149.0	155.3	35156	6.3	5.8	2C0	3.22	.07	.78	1.59	13.00											
155.3	160.0	35157	4.7	4.7	2E4	4.87	.02	2.20	7.01	15.00											
160.0	163.5	35158	3.5	3.5	2E4	4.84		2.78	6.31	16.00											
163.5	167.0	35159	3.5	3.0	2A4	3.48	.03	3.41	8.00	26.00											

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	---ASSAYS---												
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %
7.0	12.2	34511	5.2	5.2	1D4	2.86	.08	.09	.04	12.00									
12.2	18.0	34512	5.8	5.8	2H34	3.92	.24	3.56	5.39	80.00									
18.0	24.0	34513	6.0	6.0	2C0	3.07	.08	.24	.40	8.00									
24.0	29.5	34514	5.5	5.5	1H49	2.85	.08	.89	.78	18.00									
29.5	34.5	34515	5.0	5.0	1H49	3.22	.26	2.45	1.60	45.00									
34.5	39.5	34516	5.0	5.0	1H49	3.53	.19	3.84	2.59	84.00									
39.5	42.0	34517	2.5	2.5	2E0	4.51	.21	1.54	.36	65.00									
42.0	47.0	34518	5.0	5.0	2F4	4.60	.26	7.13	6.69	121.00									
47.0	52.1	34519	5.1	5.1	2F4	5.01	.15	4.53	4.91	83.00									
52.1	56.0	34520	3.9	3.9	2F4	4.40	.19	5.29	4.69	93.00									
56.0	61.0	34521	5.0	5.0	2F4	4.60	.12	6.19	6.21	92.00									
61.0	65.8	34522	4.8	4.8	2E14	4.33	.05	1.59	2.92	21.00									
65.8	69.8	34523	4.0	4.0	2E1	4.14	.04	.48	.60	11.00									
69.8	74.0	34524	4.2	4.2	2E1	4.16	.04	.29	.12	7.00									
74.0	77.8	34525	3.8	3.8	2E0	4.67	.05	.74	.51	12.00									
77.8	81.3	34526	3.5	3.5	2E0	4.78	.47	1.00	.23	16.00									
81.3	85.0	34527	3.7	3.7	2E0	4.58	.35	1.12	.30	18.00									
85.0	90.6	34528	5.6	5.6	2E1	4.58	.09	.49	.08	10.00									
90.6	95.6	34529	5.0	5.0	2E14	4.77	.04	2.33	3.71	22.00									
95.6	100.6	34530	5.0	5.0	2E8	4.51	.29	1.12	2.28	17.00									
100.6	104.7	34531	4.1	4.1	2E8	4.37	.20	1.31	1.85	17.00									
104.7	108.1	34532	3.4	3.1	2E14	4.46	.13	1.88	2.67	20.00									
108.1	112.1	34533	4.0	4.0	2E14	4.72	.17	2.04	3.41	23.00									
112.1	115.8	34534	3.7	3.7	2E1	4.70	.08	.91	.93	14.00									
115.8	119.7	34535	3.9	3.9	2E14	4.84	.14	2.46	2.22	21.00									
119.7	123.5	34536	3.8	3.8	2E14	4.07	.14	2.82	7.42	16.00									
123.5	127.6	34537	4.1	4.1	2E84	4.27	.28	3.29	5.60	11.00									
127.6	132.0	34538	4.4	4.4	2E84	4.71	.13	3.64	8.48	14.00									
132.0	137.0	34539	5.0	5.0	2E84	4.79	.15	2.42	6.21	15.00									

PAGE : 265

```
DDH: 86F-06      UTM-N: 9407.0      UTM-E: 14667.5      UTM-ELEV: 3713.7      TOTAL DEPTH: 364.0      SECTION: 118+070
RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 315 DHD CALC: 1 SS CALC: 1
```

[illegible]

PAGE : 267

[illegible]

DDH: 86F-09 UTM-N: 8438.0 UTM-E: 14223.2 UTM-ELEV: 3869.5 TOTAL DEPTH: 476.0 SECTION: 121+000
RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 315 DHD CALC: 1 SS CALC: 1

[illegible]

DDH: 86F-11 UTM-N: 9114.9 UTM-E: 14711.4 UTM-ELEV: 3739.5 TOTAL DEPTH: 337.0 SECTION: 120+000
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 315 DHD CALC: 1 SS CALC: 1

-----DEPTHS-----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
165.2	169.0	35201	3.8	3.8	2G74	4.20		5.47	7.87	95.00		.10	12	14	27						
169.0	173.5	35202	4.5	4.5	1H4	2.90		1.31	.87	24.00		.07	6	5	12						
173.5	180.9	35203	7.4	3.7	1H4	3.70		4.19	3.47	69.00		.07	16	13	29						
180.9	184.8	35204	3.9	3.9	2E4*	4.20		8.66	8.15	140.00		.24	12	19	31						
184.8	193.0	35205	8.2	6.7	1H4	3.20		2.72	2.75	14.00		1.17	5	8	13						
193.0	198.0	35206	5.0	3.9	2E46	4.50		2.07	2.47	17.00		.55	2	35	37						
198.0	202.0	35207	4.0	4.0	2E0	4.80		1.59	1.54	16.00		.03	3	37	41						
202.0	207.0	35208	5.0	4.3	2E0	4.30		.35	.15	14.00		.03	1	36	37						
207.0	211.0	35209	4.0	3.0	2E0	4.50		.72	.19	9.00			1	39	41						
211.0	217.0	35210	6.0	3.9	2E0	4.50		.31	.16	5.00			1	40	41						
217.0	223.0	35211	6.0	3.7	2E4	5.00		2.74	3.15	12.00		.21	1	39	41						
223.0	228.5	35212	5.5	5.5	2E18	4.80		.90	.73	24.00		.69	5	36	41						
228.5	233.5	35213	5.0	5.0	2E80	4.50		1.45	.40	20.00		.14	6	35	41						
233.5	238.3	35214	4.8	4.8	2E48	4.80		2.75	2.47	36.00		.17	5	36	42						
238.3	243.5	35215	5.2	5.2	2E80	4.50		.45	.33	9.00		.03	7	34	42						
243.5	246.6	35216	3.1	3.1	2GE4	4.50		4.39	4.48	73.00			7	24	31						
246.6	251.0	35217	4.4	4.4	2E0	4.30		1.14	1.14	11.00			12	28	40						
251.0	255.9	35218	4.9	4.2	2E0	4.30		.66	.56	11.00			10	31	42						
255.9	260.4	35219	4.5	4.5	2E0	4.55		.82	.56	15.00			8	33	42						
260.4	265.0	35220	4.6	4.6	2E0	4.50		1.79	1.78	20.00			6	33	40						
265.0	271.0	35221	6.0	6.0	2E0	4.80		1.33	2.19	16.00			4	36	41						
271.0	277.5	35222	6.5	5.9	2E4	4.50		2.84	3.15	26.00			2	39	42						
277.5	283.0	35223	5.5	5.5	2E814	4.50		2.15	3.27	22.00			5	32	38						
283.0	286.5	35224	3.5	3.5	2E814	4.30		3.15	4.86	18.00			5	28	33						
286.5	291.0	35225	4.5	4.5	2E814	4.30		2.27	3.05	60.00			5	32	37						
291.0	296.0	35226	5.0	5.0	2E814	4.50		2.37	4.71	7.00			5	31	37						
296.0	303.0	35227	7.0	7.0	2A43	3.80		2.75	7.83	36.00			4	17	21						
303.0	307.8	35228	4.8	4.8	2ED	4.00		1.01	.92	27.00			9	25	34						
307.8	312.2	35229	4.4	4.4	2D5	4.00		3.74	7.60	18.00			19	10	30						

DDH: 86F-12 UTM-N: 8993.8 UTM-E: 14596.9 UTM-ELEV: 3740.5 TOTAL DEPTH: 463.0 SECTION: 120+000
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 315 DHD CALC: 1 SS CALC: 1

-----DEPTHS-----						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
185.6	190.3	35230	4.7	4.7	2E341	3.70		2.17	5.20	24.00				10	17	28					
190.3	194.5	35231	4.2	3.6	2C07	3.00		.40	.20	8.00			.07	4	4	9					
194.5	199.0	35232	4.5	4.5	2C07	3.00		.26	.42	6.00			.45	4	11	15					
199.0	204.0	35233	5.0	5.0	2C37	3.70		.24	.75	4.00			.38	2	25	28					
204.0	209.0	35234	5.0	5.0	2C37	3.70		.75	2.02	10.00			.34	2	23	26					
209.0	213.9	35235	4.9	4.7	2G4	4.50		6.40	6.98	70.00			.58	4	22	26					
213.9	217.5	35236	3.6	3.6	2G4	4.80		7.36	6.56	74.00			.24	6	22	29					
217.5	222.1	35237	4.6	4.6	2G4	4.80		6.42	6.87	74.00			.14	2	20	22					
222.1	227.1	35238	5.0	4.8	2G4	4.50		7.60	6.87	90.00			.27	4	24	29					
227.1	231.7	35239	4.6	4.6	2G4	4.80		5.66	6.65	80.00			.24	1	23	24					
231.7	235.8	35240	4.1	4.1	2G4	4.80		5.86	6.89	98.00			.21	3	19	22					
235.8	238.7	35241	2.9	2.9	2H43	4.30		4.45	6.73	70.00			.14	17	15	33					
238.7	243.2	35242	4.5	4.5	1D219	3.00		.73	.84	12.00			.14	2	4	7					
243.2	247.0	35243	3.8	3.8	1D219	3.00		.52	.66	4.00			.03	2	2	4					
247.0	252.0	35244	5.0	4.6	1D219	3.00		.75	1.09	14.00			.07	3	3	7					
252.0	256.0	35245	4.0	4.0	1D19*	3.00		1.94	1.83	44.00				3	5	8					
256.0	260.7	35246	4.7	4.7	BXA	3.70		.42	3.46	94.00				14	14	28					
260.7	264.5	35247	3.8	3.8	2H43	4.50		6.46	8.88	104.00				18	17	35					
264.5	268.5	35248	4.0	4.0	2H43	4.30		6.63	8.51	98.00				26	12	39					
268.5	271.5	35249	3.0	3.0	2A4	3.30		2.37	7.24	38.00				6	6	13					
271.5	275.5	35250	4.0	4.0	2H43	4.30		5.66	7.84	74.00				16	20	37					
275.5	279.8	35251	4.3	4.3	1D419	2.90		.77	.69	18.00			.24	3	3	7					
279.8	282.8	35252	3.0	3.0	2EH	4.20		5.19	3.42	70.00			.03	13	21	35					
282.8	288.8	35253	6.0	6.0	2E4	4.80		4.26	4.47	32.00			.07	2	36	39					
288.8	292.0	35254	3.2	3.1	2G4	4.50		6.11	7.22	42.00				2	18	21					
292.0	295.7	35255	3.7	3.7	2G4	4.50		6.29	7.56	50.00				2	20	23					
295.7	301.0	35256	5.3	2.3	2F4	4.80		1.57	3.16	8.00				3	40	44					
301.0	305.0	35257	4.0	4.0	2F4	4.50		5.92	10.10	40.00				1	34	35					
305.0	309.8	35258	4.8	4.8	2F4	4.80		3.95	6.52	20.00			.03	5	34	40					
309.8	314.0	35259	4.2	4.2	2E81	4.50		.97	1.95	10.00				5	37	43					
314.0	323.2	35260	9.2	.7	2E81	5.00		1.54	1.43	10.00				5	38	43					
323.2	327.0	35261	3.8	3.5	2E4	4.80		4.11	7.00	20.00				3	37	41					
327.0	332.0	35262	5.0	5.0	2E4	4.80		2.95	4.21	20.00				3	38	42					
332.0	335.9	35263	3.9	3.9	2E4	5.00		2.25	2.67	12.00				3	39	43					
335.9	342.0	35264	6.1	2.1	2E0	4.80		1.95	2.23	10.00				3	41	45					
342.0	347.8	35265	5.8	4.6	2E4	4.80		2.32	5.33	14.00				3	39	42					
347.8	352.8	35266	5.0	5.0	2E4	5.00		2.75	5.65	16.00		2.85		2	41	43					
352.8	357.7	35267	4.9	4.9	2E0	4.30		1.37	1.44	12.00				1	33	34					
357.7	362.4	35268	4.7	4.7	2E4	5.00		3.23	5.14	22.00				1	40	42					
362.4	366.8	35269	4.4	4.4	2E4	4.80		2.66	5.15	18.00				4	35	40					
366.8	370.2	35270	3.4	3.4	2AE4	3.40		1.73	4.01	18.00				5	11	17					
370.2	374.2	35271	4.0	4.0	2AE4	3.70		3.00	5.05	30.00			.07	5	16	21					
374.2	378.4	35272	4.2	4.2	2D5	3.10		2.04	3.28	26.00				5	7	13					
378.4	383.6	35273	5.2	5.0	2D5	3.00		3.33	4.22	44.00				5	5	11					
383.6	387.9	35274	4.3	4.3	2A43	4.50		6.67	7.25	60.00			.24	2	36	38					
387.9	393.0	35275	5.1	5.1	2A4	3.40		1.84	3.69	22.00			.03	2	1	3					
393.0	398.5	35276	5.5	5.2	2A4	2.80		2.11	2.75	22.00			.03	2	1	3					
398.5	403.5	35277	5.0	5.0	2A4	2.80		1.76	4.46	30.00			.48	1		2					
403.5	407.0	35278	3.5	.5	2A4	2.70		2.28	3.72	36.00			.14	2	2	4					
407.0	411.8	35279	4.8	4.8	2A4	3.10		1.06	1.34	16.00			.38	2	2	5					
411.8	416.2	35280	4.4	4.4	2A43	4.70		8.67	8.65	129.00			.72	4	28	33					

DDH: 86F-12 UTM-N: 8993.8 UTM-E: 14596.9 UTM-ELEV: 3740.5 TOTAL DEPTH: 463.0 SECTION: 120+000
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 315 DHD CALC: 1 SS CALC: 1

-----DEPTHS-----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
416.2	420.7	35281	4.5	4.5	2A4	2.90		1.20	2.62	22.00		.51	1	5	6						
420.7	425.3	35282	4.6	4.6	2A4	3.30		1.61	3.28	34.00		.72	1	7	8						
425.3	430.0	35283	4.7	4.7	2A4	3.20		4.50	4.06	106.00		.96	1	9	11						
430.0	434.5	35284	4.5	4.5	2A4	3.30		1.17	3.33	30.00		.69		13	14						
434.5	439.0	35285	4.5	4.5	2A4	3.00		1.52	3.29	34.00		.51	1	8	9						
439.0	443.0	35286	4.0	4.0	2A4	3.00		1.31	3.34	30.00		.14	2	7	9						
443.0	448.0	35287	5.0	5.0	2A43	4.40		1.44	4.86	22.00		.27	5	15	20						
448.0	452.8	35288	4.8	4.8	2A4	3.10		1.63	4.06	26.00		.07	3	5	9						
452.8	457.4	35289	4.6	4.6	2A4	2.90		1.31	4.84	20.00		1.47	3	2	5						

PAGE : 273

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	---ASSAYS---														S.G. W.R.
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	
198.7	204.0	35290	5.3	5.0	2D47	3.30		1.58	5.04	50.00		2.43	6	8	15						
204.0	208.0	35291	4.0	4.0	2G48	4.60		6.22	6.73	122.00		.51	6	20	27						
208.0	213.0	35292	5.0	5.0	2E0	4.80		.89	1.12	14.00		.17	2	2	4						
213.0	218.2	35293	5.2	4.8	2E4	4.70		9.14	7.72	124.00		.62	5	23	29						
218.2	223.1	35294	4.9	4.9	2E4	4.70		7.46	7.39	100.00		.62	6	29	36						
223.1	227.7	35295	4.6	4.6	2E4	4.60		5.71	6.05	84.00		.58	6	30	36						
227.7	232.8	35296	5.1	5.1	2E4	4.80		8.42	8.27	104.00		.41	5	30	35						
232.8	237.6	35297	4.8	4.8	2G4	4.70		6.83	7.30	82.00		.31	3	19	23						
237.6	241.5	35298	3.9	3.9	2G4	4.70		6.33	6.34	86.00		.24	5	23	29						
241.5	245.0	35299	3.5	3.5	2E47	4.60		6.81	8.01	108.00		.17	12	19	31						
245.0	249.4	35300	4.4	4.4	2E47	4.50		7.67	9.61	134.00		.17	15	15	31						
249.4	253.7	35301	4.3	4.3	2B4	3.30		6.54	4.80	108.00		.10	5	5	11						
253.7	258.2	35302	4.5	4.5	2B4	3.00		1.74	4.84	38.00		.07	2	2	4						
258.2	262.5	35303	4.3	4.3	2B4	3.00		1.51	4.52	52.00		.07	2	1	4						
262.5	263.8	35304	1.3	1.2	2J44	4.30		20.00	5.19	758.00		.55	7	13	21						
263.8	267.3	35305	3.5	3.5	2B4	3.10		4.93	1.19	186.00			3	4	7						
267.3	272.0	35306	4.7	4.7	2B4	3.10		3.27	5.12	82.00			3	6	9						
272.0	276.0	35307	4.0	4.0	2E4	4.10		5.95	10.60	126.00		.07	8	16	24						
276.0	278.5	35308	2.5	2.5	2K4	4.20		6.80	10.30	90.00			13	18	32						
278.5	285.5	35309	7.0	6.7	2E4	4.90		1.84	2.90	22.00			2	37	40						
285.5	292.1	35310	6.6	5.0	2G42	4.60		5.15	7.24	54.00		.21	2	21	24						
292.1	294.4	35311	2.3	2.3	2G42	4.30		4.84	6.26	48.00		.07	1	25	27						
294.4	298.8	35312	4.4	4.4	2F0	4.80		2.63	3.32	30.00		.07	4	33	38						
298.8	302.8	35313	4.0	4.0	2F0	4.90		1.04	2.91	20.00		.03	2	2	5						
302.8	307.7	35314	4.9	4.9	2F4	4.90		6.49	5.87	54.00			1	36	38						
307.7	312.6	35315	4.9	4.8	2F4																

DDH: 86F-14 UTM-N: 9361.6 UTM-E: 14564.2 UTM-ELEV: 3706.9 TOTAL DEPTH: 270.0 SECTION: 118+000
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 315 DHD CALC: 1 SS CALC: 1

-----DEPTHS-----							-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.	
102.7	108.0	35333	5.3	4.7	2GL	4.20		3.82	4.50	44.00		.10	8	19	27							
108.0	111.5	35334	3.5	3.4	2J814	4.00		2.71	2.01	14.00			41		41							
111.5	118.0	35335	6.5	6.5	2E4	4.40		3.30	3.00	44.00			5	33	39							
118.0	126.0	35336	8.0	6.5	2E4	4.30		3.87	4.04	52.00			17	19	37							
126.0	132.2	35337	6.2	6.2	2E0	4.60		1.82	1.36	26.00		.27	12	28	41							
132.2	135.2	35351	3.0	3.0	2J81	4.00		1.15	1.26	8.00			43	3	46							
135.2	139.8	35338	4.6	3.3	2E4	4.50		8.26	8.46	88.00		.27	2	28	30							
139.8	144.0	35339	4.2	3.8	2E0@	4.50		.56	.35				12	26	39							
144.0	150.2	35340	6.2	6.2	2E4	4.40		2.94	3.09	28.00			4	33	38							
150.2	156.5	35341	6.3	6.3	2E44	4.30		5.91	8.23	50.00			1	33	35							
156.5	161.0	35342	4.5	4.4	2E0	4.70		1.25	1.74	16.00			6	33	40							
161.0	165.2	35343	4.2	4.2	2E0	4.70		.95	1.68	12.00			4	34	39							
165.2	170.2	35344	5.0	5.0	2E0	4.70		1.24	2.25	10.00			4	34	39							
170.2	174.7	35345	4.5	3.7	2E4	4.50		1.42	2.94	8.00			4	31	35							
174.7	180.0	35346	5.3	5.0	2E4BX	4.50		2.71	4.05	10.00			6	27	33							
180.0	185.0	35347	5.0	5.0	2E4	4.60		2.67	4.74	26.00				38	39							
185.0	190.4	35348	5.4	5.4	2E4	4.60		3.75	6.34	14.00			1	38	39							
190.4	195.0	35349	4.6	4.6	2E4	4.50		2.66	3.59	12.00				40	41							
195.0	199.5	35350	4.5	4.5	2E4	4.70		4.22	9.28	18.00			1	33	35							
199.5	204.0	35352	4.5	4.5	2E4	4.70		2.28	5.99	8.00		.21	1	38	40							
204.0	209.5	35353	5.5	5.5	2E14	4.50		2.71	5.70	10.00			3	32	36							
209.5	215.0	35354	5.5	5.5	2E4	4.80		3.33	6.72	8.00			1	37	38							
215.0	220.0	35355	5.0	5.0	2A47	3.60		3.03	5.80	38.00			17	8	26							
220.0	225.0	35356	5.0	5.0	2D57	3.10		1.47	2.80	14.00		.03	8	4	13							
225.0	229.0	35357	4.0	3.9	2C79	3.30		.11	1.18			.03	5	11	17							
229.0	233.0	35358	4.0	4.0	2C579	3.30		.44	1.35	4.00			29	4	34							
233.0	237.5	35359	4.5	4.5	2D79	3.50		1.56	5.11	16.00		.07	9	13	22							
237.5	243.5	35360	6.0	6.0	2A44	3.90		4.95	9.79	36.00		.14	2	18	21							
243.5	248.0	35361	4.5	4.5	2A44	3.20		4.05	9.18	18.00		.14	4	8	12							

DDH: 86F-15 UTM-N: 8757.8 UTM-E: 14787.0 UTM-ELEV: 3737.5 TOTAL DEPTH: 416.5 SECTION: 121+000
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 315 DHD CALC: 1 SS CALC: 1

-----DEPTHS-----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
128.0	133.5	35362	5.5	5.5	2E4	4.40		2.01	2.85	38.00		.07	9	26	35						
133.5	135.5	35363	2.0	2.0	2G4	4.30		3.50	7.25	63.00			1	17	18						
135.5	141.3	35364	5.8	3.9	2E4	4.60		6.40	8.28	110.00		.07	11	20	31						
141.3	145.1	35365	3.8	3.8	2E4	4.20		5.72	8.32	95.00		.07	14	20	34						
145.1	148.3	35366	3.2	3.2	2D43	3.70		3.79	8.49	69.00		.07	13	11	24						
148.3	153.0	35367	4.7	4.7	2C0	3.00		.17	.18	8.00			4	5	10						
153.0	157.5	35368	4.5	4.4	1H49	3.10		.21	.22	6.00			5	3	8						
157.5	162.5	35369	5.0	4.9	2C03	3.50		1.71	.50	53.00			14	18	33						
162.5	166.5	35370	4.0	4.0	1H4*9	4.00		4.33	4.27	80.00		.03	10	14	24						
166.5	172.5	35371	6.0	6.0	1H49	2.80		.39	.22	8.00			9	5	14						
172.5	177.0	35372	4.5	4.3	1E19	2.80		.25	.29	6.00		.03	1	2	4						
177.0	182.4	35373	5.4	5.4	1E19	3.00		.59	.92	10.00		.27	2	4	6						
182.4	187.0	35374	4.6	4.6	1D49	3.20		1.02	.46	21.00		.27	3	5	8						
187.0	191.8	35375	4.8	4.7	1D49	3.10		1.22	1.58	25.00		.21	3	4	7						
191.8	195.3	35376	3.5	3.4	1H49	3.70		3.64	4.30	57.00			11	13	25						
195.3	198.8	35377	3.5	3.5	1H49	3.00		1.79	.47	34.00			3	2	6						
198.8	203.8	35378	5.0	5.0	1E19	2.90		.26	.48	6.00			1	2	4						
203.8	209.8	35379	6.0	5.5	1D9	3.10		.67	1.44	11.00			5	6	11						
209.8	214.3	35380	4.5	4.5	1D9	2.90		.65	1.11	11.00			2	2	5						
214.3	219.4	35381	5.1	5.1	1D9	3.10		.97	1.09	15.00			2	5	8						
219.4	224.7	35382	5.3	4.2	2E4	4.50		4.24	4.33	51.00			2	29	31						
224.7	228.2	35383	3.5	3.5	2E4	3.40		7.18	4.71	118.00			7	9	16						
228.2	233.5	35384	5.3	2.0	2E1	4.50		2.13	1.58	27.00				38	39						
233.5	238.5	35385	5.0	1.8	2E1	4.00		.48	.28	10.00				31	32						
238.5	246.0	35386	7.5	6.2	2E1	3.70		.60	.39	30.00				25	26						
246.0	251.5	35387	5.5	5.0	2E1	4.10		1.09	.51	76.00				34	35						
251.5	258.5	35388	7.0	3.1	2E1	4.20		.47	.15	11.00			1	34	35						
258.5	264.5	35389	6.0	4.6	2E1	4.40		1.24	.97	17.00			2	35	38						
264.5	269.5	35390	5.0	3.5	2E1	4.40		1.39	1.18	17.00				37	38						
269.5	276.2	35391	6.7	4.7	2E1	4.00		.61	.95	11.00			1	34	36						
276.2	280.5	35392	4.3	4.3	2E14	4.70		2.67	1.69	30.00			2	41	43						
280.5	284.5	35393	4.0	4.0	2E1	4.70		1.24	1.98	17.00			3	39	43						
284.5	289.0	35394	4.5	4.5	2F4	5.00		6.50	7.25	30.00			4	33	38						
289.0	294.3	35395	5.3	5.3	2F4	4.50		5.44	8.12	21.00			5	30	36						
294.3	298.0	35396	3.7	3.7	2F4	4.90		3.43	6.47	17.00			3	36	40						
298.0	302.2	35397	4.2	4.2	2F4	4.60		3.49	7.74	19.00			2	36	39						
302.2	307.1	35398	4.9	4.9	2F4	4.60		4.40	8.50	22.00			5	29	35						
307.1	310.9	35399	3.8	3.8	2F4	4.60		7.75	12.97	46.00			7	23	30						
310.9	314.5	35400	3.6	3.6	2F4	4.70		7.58	11.23	60.00			7	24	32						
314.5	318.5	35401	4.0	4.0	2F4	4.70		5.79	6.80	48.00			6	28	34						
318.5	322.8	35402	4.3	4.3	2E4	4.70		2.17	3.55	17.00			5	34	39						
322.8	327.0	35403	4.2	4.2	2E4	4.70		5.82	8.71	26.00			2	33	36						
327.0	331.2	35404	4.2	4.2	2E4	5.00		2.14	5.21	13.00			1	39	40						
331.2	335.1	35405	3.9	3.9	2E0	4.90		1.03	1.91	11.00				43	44						
335.1	339.6	35406	4.5	4.5	2E0	4.90		.19	1.97	6.00				46	47						
339.6	345.5	35407	5.9	5.0	2E4	4.90		3.55	6.42	20.00				41	42						
345.5	348.8	35408	3.3	3.3	2E4	4.90		5.31	10.02	32.00			1	37	39						
348.8	353.5	35409	4.7	4.7	2E4	4.90		3.49	9.26	23.00			2	36	38						
353.5	357.5	35410	4.0	4.0	2E4	4.50		1.90	3.90	22.00			6	32	38						
357.5	360.1	35411	2.6	2.6	2H34	4.60		6.16	9.25	40.00			12	26	38						
360.1	365.5	35412	5.4	5.4	2D3	3.60		2.37	5.34	20.00			7	12	19						

DDH: 86F-15 UTM-N: 8757.8 UTM-E: 14787.0 UTM-ELEV: 3737.5 TOTAL DEPTH: 416.5 SECTION: 121+000
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 315 DHD CALC: 1 SS CALC: 1

-----DEPTHS-----							-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.	
365.5	370.5	35413	5.0	5.0	2C05	3.00		1.23	2.24	18.00			4	3	7							
370.5	375.0	35414	4.5	4.4	2A4	3.00		1.56	4.29	21.00			2	2	5							
375.0	384.0	35415	9.0	8.9	1D419	2.90		.04	.06	2.00			4	1	5							
384.0	387.8	35416	3.8	3.8	2A0	3.10		.24	.66	10.00			3	9	13							
387.8	392.7	35417	4.9	4.7	2A0	3.10		.19	.75	11.00			6	7	13							
392.7	396.8	35418	4.1	4.1	2A0	3.10		.11	.42	7.00			5	6	12							
396.8	401.4	35419	4.6	4.6	1D09	2.80		.34	.25	21.00			2	3	5							
401.4	406.5	35420	5.1	5.1	2A0	3.00		.20	.39	6.00			2	3	6							
406.5	410.7	35421	4.2	4.2	2A0	3.00		.26	1.58	8.00			3	4	8							

DDH: 86F-16 UTM-N: 9426.4 UTM-E: 14738.8 UTM-ELEV: 3706.7 TOTAL DEPTH: 297.0 SECTION: 118+00
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 315 DHD CALC: 1 SS CALC: 1

-----DEPTHS-----		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
11.0	18.5	34551	7.5	7.5	2G4	4.50		6.58	7.70	91.00		.21	3	13	17						
18.5	25.5	34552	7.0	6.7	2E14	4.60		1.69	2.45	19.00		.10		35	36						
25.5	29.5	34553	4.0	4.0	2G4	4.70		4.37	8.05	44.00		.03		26	26						
29.5	33.5	34554	4.0	4.0	2G4	4.70		4.34	7.42	44.00		.07		26	27						
33.5	37.0	34555	3.5	3.5	2E4	4.60		2.10	3.86	26.00		.17	2	37	39						
37.0	40.5	34556	3.5	3.4	2E4	4.90		3.35	4.20	27.00		.07		36	36						
40.5	45.5	34557	5.0	5.0	2C3	3.60		.11	.17	2.00		.03		28	28						
45.5	50.6	34558	5.1	5.1	2C3@	4.10		.52	.60	6.00		.10		33	34						
50.6	57.0	34559	6.4	6.4	2E1	4.30		.76	1.10	10.00		.10	1	32	33						
57.0	62.6	34560	5.6	4.2	2E1	4.90		1.40	1.54	12.00		.07		45	46						
62.6	67.8	34561	5.2	5.2	2E1	4.50		.82	.41	18.00		.17		38	39						
67.8	69.5	34562	1.7	1.7	2E14	4.00		3.94	4.49	49.00		.34	1	22	24						
69.5	75.0	34563	5.5	5.5	2E484	4.50		5.57	7.72	25.00		.10	5	28	34						
75.0	80.0	34564	5.0	5.0	2E484	4.80		9.22	13.60	45.00		.10	6	24	31						
80.0	84.6	34565	4.6	4.6	2E484	5.00		6.12	9.07	40.00		.21	7	33	40						
84.6	88.3	34566	3.7	3.7	2E8	4.80		.66	1.82	8.00		.17	6	35	42						
88.3	93.0	34567	4.7	4.7	2E1	3.90		.63	1.23	16.00		.65	1	29	31						
93.0	98.2	34568	5.2	5.2	2D443	4.60		9.81	13.63	28.00		.21	3	20	24						
98.2	101.7	34569	3.5	3.5	2C3	4.30		.16	.68	4.00		.27	1	32	33						
101.7	105.0	34570	3.3	3.3	2D3	3.90		2.93	1.99	36.00		1.51		27	28						
105.0	109.0	34571	4.0	4.0	2D3	3.70		1.41	5.33	12.00		.24	1	25	27						
109.0	113.5	34572	4.5	4.5	2D3	3.80		.53	3.76	8.00		.17	2	24	26						
113.5	116.5	34573	3.0	3.0	2C3	3.70		.38	.82	12.00		.31		28	28						
116.5	120.0	34574	3.5	3.5	2E81	4.10		.87	2.49	6.00		.10	5	28	34						
120.0	124.5	34575	4.5	4.5	2E481	4.00		8.89	16.00	17.00		.10	6	19	25						
124.5	129.5	34576	5.0	5.0	2E481	3.90		4.69	4.97	7.00		.14	4	20	25						
129.5	134.8	34577	5.3	5.3	2E481	4.00		6.01	6.53	10.00		.14	5	17	22						
134.8	139.0	34578	4.2	4.2	2E81	3.90		.16	2.28	2.00		.10	5	23	29						
139.0	144.0	34579	5.0	5.0	2E81	3.90		.14	1.10	4.00		.10	5	24	29						
144.0	149.4	34580	5.4	5.4	2E81	4.30		.10	1.80	6.00		.07	8	32	40						
149.4	152.0	34581	2.6	2.5	2C3	3.60		.29	1.91	12.00		.03	4	19	23						
152.0	154.8	34582	2.8	2.8	2E81	4.40		.24	1.56	4.00			5	36	41						
154.8	159.0	34583	4.2	4.2	2E481	4.20		2.60	6.09	6.00			5	27	33						
159.0	164.0	34584	5.0	5.0	2E481	4.40		1.22	3.40	6.00			6	29	36						
164.0	168.0	34585	4.0	4.0	2E814	4.40		1.91	2.46	8.00		.07	3	32	35						
168.0	172.6	34586	4.6	4.6	2E81	4.40		.12	1.12	4.00		.07	5	36	42						
172.6	177.0	34587	4.4	4.4	2E41	4.50		3.92	8.68	10.00		.03	2	30	32						
177.0	182.0	34588	5.0	4.5	2E41	4.70		6.71	11.96	19.00		.03	1	34	36						
182.0	187.0	34589	5.0	4.7	2EA4	4.10		1.54	5.94	8.00		.07	1	31	32						
187.0	191.0	34590	4.0	4.0	2EA4	4.10		1.84	6.84	10.00		.10		29	30						
191.0	198.0	34591	7.0	4.7	2A34	3.80		4.56	7.76	21.00			1	37	38						
198.0	202.6	34592	4.6	4.6	2A34	4.10		1.63	7.19	11.00		.07		25	26						
202.6	208.6	34593	6.0	6.0	2A34	3.80		2.75	6.05	16.00		.07		20	21						
208.6	215.0	34594	6.4	6.4	2E4	4.70		5.36	9.42	6.00		.03	1	36	37						
215.0	222.5	34595	7.5	7.5	2D345	3.80		3.56	7.56	10.00		.17	3	19	22						
222.5	228.2	34596	5.7	5.7	2C0	3.20		.61	1.12	24.00		.14	6	9	16						
228.2	234.0	34597	5.8	5.8	2D0	.50		.15	5.94	6.00		.03	3	13	17						
234.0	238.7	34598	4.7	4.7	2A34	4.00		5.15	12.32	38.00		.17	2	19	22						
238.7	244.8	34599	6.1	6.1	2E14	4.00		3.27	4.34	28.00		.14	5	26	31						
244.8	249.0	34600	4.2	4.2	2C0	3.30		.77	.61	15.00		.14	4	7	12						
249.0	253.8	35083	4.8	4.7	2C0	3.20		.26	.51	9.00		.14	3	12	16						

DDH: 86F-16 UTM-N: 9426.4 UTM-E: 14738.8 UTM-ELEV: 3706.7 TOTAL DEPTH: 297.0 SECTION: 118+00
RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 315 DHD CALC: 1 SS CALC: 1

-----DEPTHS----						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
253.8	259.2	35084	5.4	5.4	2C5	2.90		.49	1.72	13.00		.34	5	6	11						
259.2	265.5	35085	6.3	6.3	1D194	2.80		.54	.18	17.00		.17	3	2	5						
265.5	271.5	35086	6.0	6.0	1D194	2.80		.22	.40	7.00		.03	1	2	3						

DDH: 86F-17 UTM-N: 9534.4 UTM-E: 14831.4 UTM-ELEV: 3708.7 TOTAL DEPTH: 325.0 SECTION: 118+070
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 315 DHD CALC: 1 SS CALC: 1

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. U.R.
7.0	11.5	35470	4.5	4.5	2GAC	3.60		4.20	12.52	42.00			3	15	19						
11.5	17.0	35471	5.5	4.7	2A4	3.50		2.14	5.84	26.00			2	16	19						
17.0	21.8	35472	4.8	4.8	2A4	3.60		3.15	6.07	68.00				18	19						
21.8	26.0	35473	4.2	4.2	2C3	4.10		.35	1.25	12.00			1	36	37						
26.0	31.0	35474	5.0	5.0	2C3	4.10		.13	.72	6.00			2	36	39						
31.0	36.0	35475	5.0	5.0	2C3	4.00		.39	1.37	8.00			4	30	34						
36.0	42.0	35476	6.0	6.0	2C3	4.00		.31	.89	8.00			3	30	34						
42.0	48.0	35477	6.0	5.9	2C3	3.90		.19	1.12	6.00			2	29	31						
48.0	53.2	35478	5.2	5.0	2D3	4.20		1.96	4.38	16.00			1	30	32						
53.2	59.0	35479	5.8	5.8	2C09	3.30		1.08	1.30	36.00			3	12	16						
59.0	64.0	35480	5.0	5.0	2C09	3.50		.06	.48	8.00				25	26						
64.0	70.0	35481	6.0	5.3	2D0	3.70		.02	.18	6.00			2	26	28						
70.0	76.0	35482	6.0	6.0	2C0	3.50		1.50	4.24	16.00			2	18	20						
76.0	81.0	35483	5.0	5.0	2E10	4.00		.10	.99	2.00				30	31						
81.0	86.0	35484	5.0	5.0	2E10	3.90		.25	.99	8.00			2	28	30						
86.0	93.0	35485	7.0	7.0	2E10	4.00		.63	2.04	8.00				33	34						
93.0	99.0	35486	6.0	6.0	2E10	3.90		.71	1.88	10.00				29	30						
99.0	105.0	35487	6.0	6.0	2CE	3.50		2.09	3.72	26.00			1	21	22						
105.0	111.5	35488	6.5	6.5	2CE	4.00		.10	.78	16.00			1	29	30						
111.5	116.0	35489	4.5	4.5	2C3	4.00		.05	.73	14.00			1	30	31						
116.0	122.0	35490	6.0	6.0	2C3	4.00		.07	1.21	16.00				30	31						
122.0	127.5	35491	5.5	5.5	2C3	4.10		.06	2.49	8.00				32	33						
127.5	132.5	35492	5.0	5.0	2C3	4.10		.04	2.46	4.00			2	30	33						
132.5	137.5	35493	5.0	5.0	2C3	3.90		.87	2.48	12.00			1	27	29						
137.5	143.0	35494	5.5	5.5	2C3	3.90		.32	2.33	8.00			1	27	28						
143.0	146.8	35495	3.8	3.8	2C3	4.10		.03	.41	4.00			1	32	34						
146.8	152.0	35496	5.2	5.2	2C3	4.00		.05	1.43	4.00			1	29	31						
152.0	156.5	35497	4.5	4.5	2C3	3.90		.28	2.07	6.00				27	28						
156.5	160.0	35498	3.5	3.5	2E1	3.90		.08	2.65	4.00				25	26						
160.0	164.0	35499	4.0	4.0	2E14	4.00		2.25	4.22	10.00			1	23	24						
164.0	168.7	35500	4.7	4.7	2D354	3.90		5.68	6.68	26.00			3	15	18						
168.7	173.0	35141	4.3	4.3	2D354	3.80		3.39	9.43	20.00			1	23	24						
173.0	178.0	35142	5.0	5.0	2D35	3.50		2.95	6.77	28.00			3	17	20						
178.0	183.0	35143	5.0	5.0	2AD	3.20		1.54	2.76	22.00			3	10	14						
183.0	188.0	35144	5.0	5.0	2C05	3.10		1.12	2.60	16.00			2	4	6						
188.0	193.0	35145	5.0	5.0	2C05	2.90		.36	.98	10.00			3	8	11						
193.0	198.0	35146	5.0	5.0	2C05	3.00		.63	1.81	12.00			2	9	11						
198.0	203.0	35147	5.0	5.0	2C05	3.20		.29	.95	6.00			6	14	20						
203.0	211.5	35148	8.5	7.5	2C05	3.30		.69	2.68	14.00			4	15	19						
211.5	218.5	35149	7.0	5.3	2C05	3.30		.36	.35	18.00			4	16	20						
218.5	223.0	35150	4.5	3.4	2D05	3.50		3.23	5.10	40.00			4	15	20						
223.0	226.0	35087	3.0	3.0	2D05	3.10		3.24	2.37	44.00			6	10	16						
226.0	230.6	35088	4.6	4.6	2B4	2.90		2.04	6.72	30.00			2	1	4						
230.6	235.5	35089	4.9	4.9	2B4	2.80		1.86	3.47	24.00			2	2	5						
235.5	240.3	35090	4.8	4.8	2B4	3.00		4.46	4.12	50.00			3	3	6						
240.3	244.7	35091	4.4	4.4	2B4	2.90		3.64	5.15	36.00			2	2	5						
244.7	249.0	35092	4.3	4.3	2B4	3.00		3.43	8.66	46.00			3	1	4						
249.0	252.5	35093	3.5	3.5	2A4	3.00		4.20	9.31	58.00			2	2	4						
252.5	255.5	35094	3.0	3.0	2B45	3.00		1.10	3.35	32.00			2	3	6						
255.5	266.0	35095	10.5	9.3	1D419	3.00		1.99	4.48	94.00			3	2	5						
266.0	270.7	35096	4.7	4.7	2B45	3.00		3.81	6.12	76.00			2	2	5						

DDH: 86F-17 UTM-N: 9534.4 UTM-E: 14831.4 UTM-ELEV: 3708.7 TOTAL DEPTH: 325.0 SECTION: 118+070
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 315 DHD CALC: 1 SS CALC: 1

-----DEPTHS-----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
270.7	275.3	35097	4.6	4.6	2B45	3.00		3.29	5.15	32.00			3	3	7						
275.3	280.2	35098	4.9	4.9	2B45	3.00		4.67	6.78	60.00			2	1	4						
280.2	285.1	35099	4.9	4.9	2B45	3.10		4.28	10.51	52.00			2	1	3						
285.1	290.0	35100	4.9	4.9	2B45	3.00		4.87	4.99	50.00			3	2	6						
290.0	295.1	04964	5.1	5.1	2B45	3.20		2.95	6.76	42.00			3	1	5						
295.1	300.0	04965	4.9	4.9	2B45	3.00		2.09	7.27	38.00			2	1	3						
300.0	305.0	04966	5.0	5.0	2C0	3.00		.86	2.52	19.00			3	4	7						

DDH: 86F-18 UTM-N: 9363.8 UTM-E: 14961.4 UTM-ELEV: 3704.5 TOTAL DEPTH: 277.0 SECTION: 120+000
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 315 DHD CALC: 1 SS CALC: 1

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
14.0	18.4	35104	4.4	4.4	2E18	3.90		.18	1.32	4.00		.21	4	27	32						
18.4	22.8	35105	4.4	4.4	1H4*	3.30		1.74	.48	25.00		.89	5	14	20						
22.8	29.0	35106	6.2	5.8	2E18	3.90		.19	.70	8.00		.24	5	28	34						
29.0	35.0	35107	6.0	6.0	2E18	4.00		.58	.71	6.00		.10	2	32	34						
35.0	39.8	35108	4.8	4.8	2A34	3.40		3.20	6.01	28.00		.27	4	14	19						
39.8	42.6	35109	2.8	2.8	2D7	3.30		3.14	6.05	32.00		.58	15	4	20						
42.6	46.0	35110	3.4	3.4	2C7	3.40		.50	.20	17.00		.51	16	6	23						
46.0	50.3	35111	4.3	4.3	1D4	3.10		1.28	.07	38.00		.99	3	4	8						
50.3	55.6	35112	5.3	4.4	10Q9	3.10		.29	.09	12.00		.65	2	14	16						
55.6	60.6	35113	5.0	5.0	2E18	3.60		.90	2.32	40.00		.38	5	18	24						
60.6	65.6	35114	5.0	5.0	2E18	3.90		.29	1.15	30.00		.10	1	29	30						
65.6	70.6	35115	5.0	5.0	2E18	3.90		.08	1.15	6.00		.07	2	30	32						
70.6	75.6	35116	5.0	5.0	2E18	3.80		.05	.69	6.00		.10	6	29	35						
75.6	80.6	35117	5.0	5.0	2E18	3.80		.56	.84	16.00		.07	2	29	31						
80.6	85.6	35118	5.0	5.0	2E18	4.10		.22	1.03	4.00		.07	1	32	34						
85.6	90.6	35119	5.0	5.0	2E18	3.70		.23	1.01	6.00		.21	1	27	28						
90.6	94.6	35120	4.0	4.0	2E18	3.80		.19	1.83	4.00		.14	1	29	30						
94.6	100.1	35121	5.5	5.5	2E18	4.20		.12	.72	6.00		.17	1	31	32						
100.1	104.0	35122	3.9	3.9	2E18	4.10		.06	.18	4.00		.14		34	34						
104.0	108.5	35123	4.5	4.5	2E18	4.00		.53	.28	14.00		.24		36	36						
108.5	113.8	35124	5.3	5.3	2E18	4.00		1.09	.46	20.00		.21		26	27						
113.8	118.0	35125	4.2	3.0	2E18	4.20		.17	.50	8.00		.21	1	37	38						
118.0	123.0	35126	5.0	5.0	2E18	4.50		.44	1.71	6.00		.07	5	30	35						
123.0	128.0	35127	5.0	5.0	2E18	3.80		.43	.86	4.00			6	26	32						
128.0	132.1	35128	4.1	4.1	2E18	3.90		.06	1.29	6.00			9	28	38						
132.1	135.0	35129	2.9	2.9	2E18	4.40		.09	.30	8.00		.10	7	34	41						
135.0	139.8	35130	4.8	4.8	2E1	4.00		.32	.91	10.00		.17	2	30	33						
139.8	144.0	35131	4.2	4.2	2E1	4.10		.39	1.68	8.00		.17	1	33	35						
144.0	148.5	35132	4.5	.0	2E1	4.50		.24	1.98	4.00		.10	3	35	39						
148.5	152.0	35133	3.5	.0	2E1	4.40		1.13	2.58	4.00		.07	3	34	37						
152.0	156.0	35134	4.0	4.0	2E14	4.20		1.80	4.14	6.00		.07	1	29	31						
156.0	160.0	35135	4.0	4.0	2E1	4.00		.40	1.80	4.00		.10	1	30	31						
160.0	165.2	35136	5.2	5.2	2E1	4.10		1.06	2.57	8.00		.17	1	28	30						
165.2	167.6	35137	2.4	2.4	2D0	3.90		2.09	6.67	20.00		.24	2	20	22						
167.6	171.0	35138	3.4	3.4	2D4	3.90		3.45	8.19	28.00		.24	3	20	23						
171.0	174.5	35139	3.5	3.5	2E4	4.90		7.01	19.30	58.00		.31	3	27	30						
174.5	178.2	35422	3.7	3.7	2E4	5.00		4.10	9.31	32.00			1	36	37						
178.2	183.6	35423	5.4	2.9	1D49	2.90		.80	.93	12.00			2	3	5						
183.6	190.0	35424	6.4	6.4	2D0	2.90		1.46	3.56	24.00			4	3	7						
190.0	195.3	35425	5.3	5.3	2D0	3.10		1.11	3.59	20.00			6	3	10						
195.3	199.7	35426	4.4	4.4	10Q9	3.00		3.63	5.74	80.00			6	1	8						
199.7	202.0	35427	2.3	2.3	2D0	2.90		1.00	4.26	26.00			1	1	3						
202.0	206.7	35140	4.7	4.7	2D0	3.00		2.19	3.63	52.00		.51	2	2	4						
206.7	211.1	35428	4.4	4.4	2A0	2.90		1.62	2.36	22.00			2	2	4						
211.1	215.4	35429	4.3	4.3	2A4	3.10		3.60	7.39	74.00			4	6	11						
215.4	220.1	35430	4.7	4.7	2A4	3.10		2.79	5.76	40.00			2	5	8						
220.1	225.1	35431	5.0	5.0	2A4	3.00		1.09	3.76	18.00			1	5	6						
225.1	229.1	35432	4.0	4.0	2D5	3.10		1.47	4.87	30.00			1	4	5						
229.1	234.0	35433	4.9	4.9	2D5	3.00		1.07	4.20	16.00			1	3	5						
234.0	238.2	35434	4.2	4.2	2D5	3.00		1.71	5.05	24.00			2	2	4						
238.2	243.2	35435	5.0	5.0	2D5	3.00		2.49	6.82	36.00			2	1	4						

DDH: 86F-18 UTM-N: 9363.8 UTM-E: 14961.4 UTM-ELEV: 3704.5 TOTAL DEPTH: 277.0 SECTION: 120+000
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 315 DHD CALC: 1 SS CALC: 1

-----DEPTHS-----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
243.2	247.7	35436	4.5	4.5	2D5	3.10		4.66	3.90	155.00			1	3	5						
247.7	251.9	35437	4.2	4.2	2D5	3.20		3.40	3.98	74.00			3	4	8						
251.9	256.1	35438	4.2	4.2	2C0	3.20		.34	1.12	14.00			2	4	7						
256.1	260.3	35439	4.2	4.2	2C0	3.00		1.25	.21	24.00			3	3	7						
260.3	265.0	35440	4.7	4.7	2C0	2.90		1.57	.56	54.00			2	3	6						

DDH: 86F-19 UTM-N: 9300.0 UTM-E: 14898.0 UTM-ELEV: 3702.6 TOTAL DEPTH: 313.0 SECTION: 120+000
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 315 DHD CALC: 1 SS CALC: 1

-----DEPTHS-----						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
100.9	105.0	35441	4.1	4.1	2D5	3.50		.62	4.35	10.00			2	17	20						
105.0	111.7	35442	6.7	6.7	2C35	3.80		.18	1.08	6.00			1	28	30						
111.7	117.0	35443	5.3	5.3	2E810	4.20		.12	.75	6.00			6	30	36						
117.0	122.6	35444	5.6	5.6	2E180	4.00		.05	.99	4.00			4	30	34						
122.6	127.0	35445	4.4	4.4	2C38	3.90		.04	1.76	4.00			7	22	29						
127.0	132.3	35446	5.3	5.3	2C38	3.90		.35	2.16	4.00			7	25	33						
132.3	137.0	35447	4.7	4.7	2C38	4.00		.70	1.71	6.00			6	25	31						
137.0	141.0	35448	4.0	4.0	2C38	3.90		1.00	1.99	14.00			8	26	34						
141.0	145.2	35449	4.2	4.2	2C38	3.60		2.77	1.21	56.00			4	19	24						
145.2	151.1	35450	5.9	5.9	2E81	4.10		.47	2.15	10.00			6	29	36						
151.1	154.4	35451	3.3	3.3	2E41	4.20		5.63	10.00	16.00			2	27	30						
154.4	158.3	35452	3.9	3.9	2E41	4.20		4.26	9.46	12.00			2	26	29						
158.3	164.0	35453	5.7	5.7	2D354	3.60		2.82	8.13	18.00			2	18	20						
164.0	170.5	35454	6.5	6.5	2D354	3.50		2.62	9.46	22.00			3	17	21						
170.5	175.7	35455	5.2	5.1	2E4	4.80		3.33	8.29	22.00			3	34	38						
175.7	178.6	35456	2.9	2.9	2A34	3.90		4.03	11.90	38.00			2	20	23						
178.6	183.5	35457	4.9	4.9	2A0	2.90		1.41	1.73	20.00			2	2	5						
183.5	188.9	35458	5.4	4.7	2A0	3.00		1.05	2.19	16.00			4	8	12						
188.9	192.0	35459	3.1	3.1	2A0	2.90		.55	2.26	12.00			1	18	20						
192.0	199.3	35460	7.3	7.3	2D5	3.10		.97	3.66	16.00			2	8	11						
199.3	204.0	35461	4.7	4.7	2C0	2.80		.16	.17	14.00			2	3	5						
204.0	209.0	35462	5.0	4.9	2C0	3.00		.07	.12	6.00			3	4	8						
209.0	214.0	35463	5.0	4.7	2C0	3.00		.25	.71	10.00			3	4	7						
214.0	224.0	35464	10.0	10.0	1D419	2.80		.60	.39	14.00			2	1	3						
224.0	233.5	35465	9.5	9.5	1D419	2.80		.22	.31	6.00			2	2	4						
233.5	243.0	35466	9.5	9.5	1D419	2.90		.24	.22	12.00			2	1	4						
243.0	251.0	35467	8.0	8.0	1D29	2.80		.10	.19	2.00			2	1	3						
251.0	259.0	35468	8.0	7.7	1D419	2.80		.38	.73	8.00			2	1	4						
259.0	267.0	35469	8.0	8.0	1D419	2.80		.36	.83	8.00			3	2	6						

DDH: 86F-20 UTM-N: 9350.7 UTM-E: 14843.4 UTM-ELEV: 3705.4 TOTAL DEPTH: 257.0 SECTION: 119+070
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 315 DHD CALC: 1 SS CALC: 1

-----DEPTHS-----						-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
11.0	21.8	10653	10.8	9.9	2E4@	4.10		4.14	6.46	48.00			2	27	30						
21.8	27.0	10654	5.2	4.1	2E1	4.60		1.28	1.43	16.00			1	38	40						
27.0	30.5	10655	3.5	2.3	2E1	4.40		.19	.31	8.00			1	35	37						
30.5	36.5	10656	6.0	5.4	2A3	3.60		.29	.83	6.00				24	24						
36.5	41.5	10657	5.0	4.3	2A34	3.50		1.07	4.92	16.00			1	19	20						
41.5	44.6	10658	3.1	2.7	2C3	4.00		.87	1.90	14.00			1	31	32						
44.6	49.0	10659	4.4	4.2	2C3	4.20		1.07	2.08	6.00			7	29	37						
49.0	54.5	10660	5.5	5.2	2E4	4.40		1.80	4.19	8.00			7	30	38						
54.5	59.5	10661	5.0	4.6	2E4	4.20		1.96	3.99	8.00			6	28	35						
59.5	64.0	10662	4.5	4.4	2E4	4.40		2.57	4.14	12.00			8	29	37						
64.0	68.5	10663	4.5	4.5	2E0	4.50		1.22	2.11	6.00			8	30	39						
68.5	72.7	10664	4.2	4.1	2E0	4.10		.07	1.64	4.00			6	31	37						
72.7	78.0	10665	5.3	5.1	2E0	4.20		.03	.67	2.00			2	34	37						
78.0	83.0	10666	5.0	4.9	2E0	4.20		.21	1.89	4.00			4	32	36						
83.0	87.5	10667	4.5	4.3	2E0	4.20		.24	.63	6.00			1	34	36						
87.5	93.0	10668	5.5	5.4	2A34	3.70		2.21	5.23	8.00			1	24	26						
93.0	97.2	10669	4.2	4.1	2A3	3.80		.36	2.15	4.00			2	28	30						
97.2	101.8	10670	4.6	4.3	2A34	3.30		2.96	5.78	36.00			2	11	14						
101.8	106.8	10671	5.0	4.8	2A34	3.70		1.23	3.22	14.00			1	33	35						
106.8	113.0	10672	6.2	5.1	2E1	4.00		.43	3.37	6.00			5	29	34						
113.0	117.0	10673	4.0	3.2	2E1	3.80		.14	1.72	4.00			5	28	33						
117.0	121.2	10674	4.2	2.5	2E81	3.80		.06	1.01	6.00			5	26	31						
121.2	126.5	10675	5.3	5.1	2E81	3.80		.09	1.63	2.00			4	28	32						
126.5	131.8	10676	5.3	5.2	2E81	4.00		.06	1.74	4.00			6	30	36						
131.8	136.8	10677	5.0	4.9	2C3	3.60		.10	.83	4.00			5	23	28						
136.8	141.0	10678	4.2	3.4	2C3	3.90		.11	1.65	4.00			7	26	33						
141.0	145.5	10679	4.5	4.4	2C3	4.10		.20	2.38	10.00			7	28	36						
145.5	150.5	10680	5.0	4.7	2D3	3.90		1.86	2.89	38.00			5	26	31						
150.5	155.0	10681	4.5	3.2	2E1	4.40		.30	1.27	6.00			4	35	39						
155.0	158.6	10682	3.6	3.5	2E1	4.30		.05	1.18	2.00			3	36	40						
158.6	162.0	10683	3.4	3.2	2E4	4.20		.35	1.24	2.00			3	35	38						
162.0	167.5	10684	5.5	5.3	2E4	4.50		3.54	5.94	8.00			3	34	38						
167.5	173.0	10685	5.5	4.8	2A4	4.50		2.86	6.41	8.00			3	34	37						
173.0	179.0	10686	6.0	3.8	2A4	3.70		3.59	8.93	18.00			2	20	22						
179.0	184.1	10687	5.1	4.2	2A4	3.60		6.27	12.50	44.00			3	13	16						
184.1	190.0	10688	5.9	4.9	2A4	4.00		4.58	11.20	24.00			1	26	28						
190.0	194.7	10689	4.7	3.5	2C0	3.00		.71	1.60	40.00			2	8	11						
194.7	200.8	10690	6.1	4.7	2C0	3.10		.50	1.71	8.00			3	9	13						
200.8	206.7	10691	5.9	5.1	2C0	3.10		.90	2.78	16.00			2	11	14						
206.7	211.0	10692	4.3	4.2	2C0	2.80		.96	1.83	14.00			2	2	4						
211.0	216.0	10693	5.0	3.3	2C0	2.90		.13	.18	4.00			3	5	8						

DDH: 86F-21 UTM-N: 9420.2 UTM-E: 14923.7 UTM-ELEV: 3708.4 TOTAL DEPTH: 299.0 SECTION: 119+070
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 315 DHD CALC: 1 SS CALC: 1

-----DEPTHS-----							-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.	
10.0	16.0	34751	6.0	5.4	2C38	3.90		.48	1.38	10.00			1	30	32							
16.0	21.0	34752	5.0	4.7	2C38	4.10		.75	1.02	8.00			4	30	35							
21.0	26.0	34753	5.0	4.7	2C38	4.10		.25	1.58	10.00			6	28	35							
26.0	31.0	34754	5.0	4.8	2C38	4.20		.37	1.19	4.00			4	30	35							
31.0	36.0	34755	5.0	4.9	2C38	4.30		.06	.56	4.00			4	35	39							
36.0	41.0	34756	5.0	4.7	2C38	4.40		.49	.37	6.00			2	37	40							
41.0	43.0	34757	2.0	1.8	2C38	3.70		.87	1.03	4.00				28	29							
43.0	47.0	10613	4.0	3.8	2C3	3.20		.71	.95	8.00			2	15	17							
47.0	52.3	34758	5.3	5.3	2A0	3.70		.70	1.22	12.00			2	22	25							
52.3	62.2	10614	9.9	7.6	1D4	3.00		.83	.13	38.00			3	2	5							
62.2	67.0	34759	4.8	4.6	2C3	3.70		1.11	2.09	14.00			2	23	26							
67.0	71.5	34760	4.5	4.2	2C3	3.90		.79	1.34	8.00			1	25	27							
71.5	75.5	34761	4.0	3.8	2C3	4.00		.15	.40	4.00				30	31							
75.5	80.5	34762	5.0	4.7	2C3	3.90		.04	1.42	2.00			1	30	32							
80.5	85.5	34763	5.0	4.9	2E81	4.50		.14	1.15	2.00			6	30	37							
85.5	90.5	34764	5.0	4.8	2E81	3.80		.63	.74	4.00			7	28	36							
90.5	95.0	10610	4.5	3.9	2E1	3.90		.76	2.07	4.00			1	28	29							
95.0	99.5	34765	4.5	4.3	2E1	3.70		.70	1.08	6.00			1	30	31							
99.5	104.0	34766	4.5	4.2	2E1	4.60		1.03	.55	14.00				35	35							
104.0	108.5	34767	4.5	4.4	2E1	3.90		3.09	.31	34.00				29	30							
108.5	114.0	10612	5.5	4.9	BXA	3.70		3.95	7.10	22.00			2	20	22							
114.0	121.7	34768	7.7	7.2	2A3	3.90		.96	1.36	12.00			1	24	25							
121.7	126.7	34769	5.0	4.7	2C38	4.10		.50	1.42	2.00			3	32	35							
126.7	131.7	34770	5.0	4.9	2C38	3.90		.34	1.36	2.00			7	24	31							
131.7	136.3	34771	4.6	4.5	2C38	4.10		.12	.37	4.00			5	31	36							
136.3	140.5	34772	4.2	3.9	2C38	4.00		.15	1.33	2.00			1	31	33							
140.5	145.5	34773	5.0	4.6	2C38	4.00		.10	1.81	2.00			2	30	32							
145.5	151.2	34774	5.7	5.5	2C38	4.20		.22	1.38	2.00			3	27	30							
151.2	155.2	10615	4.0	3.6	2E18	4.10		.67	1.97	6.00			4	28	32							
155.2	161.0	34775	5.8	5.3	2D3	4.20		.59	1.80	4.00			2	27	30							
161.0	166.0	34776	5.0	4.8	2C3	3.60		.13	2.21	4.00			1	24	26							
166.0	174.0	34777	8.0	7.1	2C3	4.00		2.50	6.00	8.00			2	24	27							
174.0	177.0	34778	3.0	2.1	2D5	4.20		6.79	6.16	74.00			2	34	36							
177.0	182.0	34779	5.0	4.4	2D5	3.80		1.07	3.20	30.00			1	18	20							
182.0	186.0	34780	4.0	3.5	2D5	3.40		2.48	5.88	24.00			3	12	16							
186.0	190.0	34781	4.0	3.3	2C5	3.30		1.57	2.10	36.00			1	5	7							
190.0	194.5	34782	4.5	4.2	2D5	2.90		1.67	3.07	22.00			2	3	6							
194.5	200.0	34783	5.5	4.0	2D5	2.90		1.19	3.02	20.00			3	6	10							
200.0	205.0	34784	5.0	4.8	2C5	3.10		1.32	2.05	18.00			3	8	12							
205.0	210.0	34785	5.0	4.9	2C5	3.20		1.04	1.72	16.00			3	9	13							
210.0	215.0	34786	5.0	4.7	2C5	3.10		2.16	1.55	42.00			2	3	5							
215.0	219.0	34787	4.0	3.5	2A4	3.30		5.00	7.42	44.00			3	15	19							
219.0	231.3	10611	12.3	10.2	2D5	2.90		1.92	5.05	32.00			4	10	15							
231.3	237.0	34788	5.7	5.4	2D5	2.80		1.05	3.65	26.00			2	2	5							
237.0	242.0	34789	5.0	4.4	2D5	2.80		.85	3.46	20.00			1	1	2							
242.0	247.0	34790	5.0	4.6	2C5	2.80		.71	2.82	16.00			1	2	3							
247.0	252.0	34791	5.0	4.9	2D5	2.90		2.00	3.96	36.00			2	3	5							
252.0	257.0	34792	5.0	4.7	2D5	2.90		.32	3.55	24.00			1	4	6							
257.0	264.0	34793	7.0	6.3	2D5	2.90		1.52	4.43	26.00			2	3	5							
264.0	269.0	34794	5.0	4.1	2C5	2.90		.84	3.13	22.00			1	2	4							
269.0	272.0	34795	3.0	2.8	2D5	2.90		1.63	3.47	24.00			2	3	6							

DDH: 86F-21 UTM-N: 9420.2 UTM-E: 14923.7 UTM-ELEV: 3708.4 TOTAL DEPTH: 299.0 SECTION: 119+070
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 315 DHD CALC: 1 SS CALC: 1

-----DEPTHS----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
272.0	277.5	34796	5.5	4.6	2C5	2.90		.27	.28	10.00			2	3	6						
277.5	280.7	34797	3.2	2.9	1D419	2.90		.62	1.20	26.00			3	3	6						
280.7	289.0	10616	8.3	7.5	1D419	2.80		1.03	1.92	8.00			2	1	4						
289.0	296.5	34798	7.5	7.1	1D419	2.90		2.11	.97	22.00			2	3	6						
296.5	299.0	34799	2.5	2.3	1D419	3.00		3.45	1.85	40.00			4	7	11						

DDH: 86F-22 UTM-N: 9260.3 UTM-E: 14657.5 UTM-ELEV: 3708.4 TOTAL DEPTH: 327.0 SECTION: 119+000
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 315 DHD CALC: 1 SS CALC: 1

-----DEPTHS-----							-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.	
104.3	108.2	10629	3.9	3.7	1H0	3.00		1.98	3.28	44.00			2	3	5							
108.2	110.4	10630	2.2	2.1	2G74	4.30		4.27	6.49	84.00			20	10	30							
110.4	115.0	10631	4.6	3.9	1H0	3.20		2.82	2.26	44.00			7	10	18							
115.0	117.5	10632	2.5	2.4	2G7	4.00		3.73	6.00	68.00			12	16	28							
117.5	123.0	10633	5.5	5.3	1H0	4.40		2.46	3.80	46.00			8	12	20							
123.0	131.2	10634	8.2	7.9	1H0	3.00		1.37	.95	18.00			5	3	9							
131.2	135.0	10635	3.8	3.7	2G74	4.30		5.74	7.63	64.00			4	17	22							
135.0	141.5	10636	6.5	6.1	2E4	4.50		3.44	2.90	48.00			6	29	35							
141.5	146.8	10637	5.3	5.0	2E0	4.50		1.33	1.15	14.00			5	28	34							
146.8	152.2	10638	5.4	5.2	2E0	4.60		1.13	.40	24.00			10	32	42							
152.2	156.5	10639	4.3	4.2	2E4\$	4.50		5.11	5.51	22.00			12	26	38							
156.5	160.8	10640	4.3	4.1	2E4\$	4.40		4.12	4.12	26.00			13	24	37							
160.8	165.2	10641	4.4	4.3	2E\$	4.30		.45	.20	6.00			9	31	41							
165.2	170.1	10642	4.9	4.7	2E84	4.70		2.23	2.69	30.00			3	37	41							
170.1	174.5	10643	4.4	4.2	2E80	4.70		2.06	1.62	50.00			7	34	41							
174.5	179.0	10644	4.5	4.5	2E80	4.40		1.89	.79	36.00			10	30	41							
179.0	183.3	10645	4.3	4.1	2E84	4.40		2.83	2.10	48.00			12	27	40							
183.3	188.7	10646	5.4	5.0	2E84	4.40		2.38	3.17	34.00			14	28	42							
188.7	192.0	10647	3.3	2.9	2E4	4.80		3.18	4.56	28.00			2	35	38							
192.0	196.0	10648	4.0	3.6	2E0	4.10		.85	2.39	18.00			4	29	33							
196.0	199.5	10649	3.5	2.5	2E4	4.60		4.18	5.47	32.00			3	32	36							
199.5	203.7	10650	4.2	3.6	2E4	4.70		2.57	5.33	24.00			2	35	38							
203.7	206.0	10652	2.3	1.8	2E4	4.70		5.21	5.96	32.00				36	37							
206.0	209.6	10617	3.6	3.4	2D5	3.70		3.77	4.11	34.00			3	20	23							
209.6	214.4	10601	4.8	4.5	2D59	2.90		1.03	4.21	24.00			2	2	5							
214.4	218.7	10602	4.3	3.9	2C59	3.10		.33	2.41	10.00			6	9	16							
218.7	223.7	10603	5.0	4.8	2C59	3.10		1.07	2.07	22.00			6	8	14							
223.7	228.5	10604	4.8	4.8	2C59	2.90		.84	1.63	16.00			1	2	4							
228.5	232.6	10626	4.1	3.8	2C0	2.90		.71	.72	11.00			2	2	5							
232.6	236.5	10627	3.9	3.1	1CD4	2.90		.03	.10				3	1	4							
236.5	240.3	10605	3.8	3.3	1CD4	2.90		.03	.03	4.00			3		4							
240.3	244.7	10606	4.4	4.2	1CD4	2.90		.02	.12	2.00			5	2	7							
244.7	248.8	10607	4.1	3.8	1CD4	2.80		.06	.05	4.00			3	1	4							
248.8	254.5	10628	5.7	5.6	2C0	2.90		.83	1.07	10.00			2	2	4							
254.5	258.0	10608	3.5	3.2	2A0	2.90		.68	2.91	16.00			4	4	8							
258.0	262.0	10609	4.0	3.8	2A0	2.90		.75	2.23	16.00			3	1	5							
262.0	267.0	10618	5.0	4.8	2C0	2.70		.53	1.65	8.00			2	2	4							
267.0	272.0	10619	5.0	4.7	2C0	2.80		1.11	1.24	12.00			2	3	6							
272.0	278.5	10620	6.5	5.9	2A70	2.90		.41	1.30	8.00			3	3	7							
278.5	284.0	10621	5.5	5.4	2A70	2.80		.80	1.48	16.00			4		5							
284.0	290.7	10622	6.7	6.4	2A70	2.90		.52	1.55	12.00			3	1	5							
290.7	297.0	10623	6.3	5.9	2A70	2.80		.66	2.31	18.00			3	2	5							
297.0	302.0	10624	5.0	4.8	2DJ4	3.90		33.60	2.43	276.00			2	1	4							
302.0	306.0	10625	4.0	3.7	2L14	2.80		.89	1.59	17.00			2	1	3							

DDH: 86F-23 UTM-N: 9181.7 UTM-E: 14980.9 UTM-ELEV: 3705.1 TOTAL DEPTH: 387.0 SECTION: 121+000
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 315 DHD CALC: 1 SS CALC: 1

-----DEPTHS-----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
106.0	111.0	04967	5.0	4.9	2E4	4.10		3.58	6.30	57.00			2	25	27						
111.0	116.0	04968	5.0	4.7	2E4	4.70		9.96	8.75	167.00			4	22	26						
116.0	122.5	04969	6.5	4.4	2E4	3.70		2.66	10.90	19.00			3	14	17						
122.5	127.0	04970	4.5	4.3	2E4	3.90		5.02	10.10	55.00			4	24	29						
127.0	132.0	04971	5.0	4.9	2A3	3.80		.93	1.09	11.00			2	24	27						
132.0	136.5	04972	4.5	4.1	2E0	4.60		.25	.36	8.00			2	40	42						
136.5	140.0	04973	3.5	3.5	2E0	4.70		.64	.86	8.00			1	40	41						
140.0	144.5	04974	4.5	4.1	2A34	3.90		1.32	4.99	9.00			1	23	24						
144.5	148.7	04975	4.2	4.0	2A34	3.80		2.10	6.11	19.00			1	21	23						
148.7	152.7	04976	4.0	3.8	2A3	3.80		.48	1.80	11.00				30	31						
152.7	156.7	04977	4.0	3.9	2A3	3.90		.50	1.30	9.00			1	29	30						
156.7	161.5	04978	4.8	4.5	2E81	4.20		.57	2.11	6.00			6	30	36						
161.5	166.5	04979	5.0	4.3	2E81	4.20		1.31	2.36	8.00			8	30	39						
166.5	170.8	04980	4.3	3.0	2E81	4.20		.71	1.89	8.00			7	28	35						
170.8	177.0	04981	6.2	5.8	2E1	4.10		.08	.61	9.00				35	35						
177.0	183.0	04982	6.0	4.2	2E1	3.80		.59	.72	9.00			1	28	29						
183.0	189.0	04984	6.0	5.6	2D34	3.40		3.34	8.62	20.00			2	14	17						
189.0	193.2	04983	4.2	3.8	2C35	3.40		.90	2.57	10.00			5	18	24						
193.2	198.0	04985	4.8	4.5	2C35	3.60		.38	.79	20.00			9	21	30						
198.0	204.0	04986	6.0	5.7	2D45	3.80		3.38	5.94	20.00			5	7	13						

DDH: 86F-24 UTM-N: 9051.2 UTM-E: 14853.9 UTM-ELEV: 3710.2 TOTAL DEPTH: 391.0 SECTION: 121+000
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 315 DHD CALC: 1 SS CALC: 1

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													
FROM	TO						Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %
130.6	135.0	10738	4.4	4.2	2D0	3.50		2.81	5.81	56.00				7	15	23				
135.0	142.3	10739	7.3	5.8	2CD	2.90		.46	1.05	16.00				3	6	9				
142.3	146.0	10740	3.7	3.5	2G4	4.50		4.81	6.58	72.00				1	20	22				
146.0	150.0	10741	4.0	3.7	2F64	4.70		6.24	5.45	76.00				2	27	30				
150.0	160.6	10742	10.6	4.5	2F64	4.60		9.23	8.61	128.00				4	18	23				
160.6	166.5	10743	5.9	5.5	2E4	4.70		2.48	1.80	32.00				1	40	42				
166.5	171.5	10744	5.0	4.7	2EG4	4.70		4.69	6.56	64.00					33	34				
171.5	175.5	10745	4.0	3.5	2E4	4.70		3.53	4.97	44.00				2	35	37				
175.5	180.0	10746	4.5	3.6	2E48	4.80		3.16	3.84	32.00				4	30	34				
180.0	184.0	10747	4.0	1.5	2E48	4.80		3.80	4.17	38.00				2	37	40				
184.0	192.5	10748	8.5	3.3	2E4	4.60		2.90	3.67	34.00				1	39	41				
192.5	199.5	10749	7.0	6.3	2E0	4.50		1.26	.77	20.00					39	40				
199.5	205.0	10750	5.5	4.7	2E0	4.60		1.06	.90	14.00					41	41				
205.0	211.0	04987	6.0	4.6	2E4	4.60		2.27	3.49	26.00				1	35	37				
211.0	217.0	04988	6.0	5.6	2E14	4.70		3.35	2.76	36.00				1	39	40				
217.0	221.5	04989	4.5	4.3	2E01	4.60		1.28	.45	16.00					38	38				
221.5	226.3	04990	4.8	4.1	2E14	4.70		2.97	3.93	34.00				1	36	37				
226.3	232.0	04991	5.7	5.6	2D3	4.40		3.07	5.72	48.00				4	29	34				
232.0	238.0	04992	6.0	5.9	2D3	4.40		2.07	2.29	16.00				5	34	40				
238.0	243.5	04993	5.5	5.1	2C3	3.90		1.20	1.10	20.00				1	30	32				
243.5	247.0	04994	3.5	3.5	2E80	4.20		.47	.85	6.00				10	31	41				
247.0	250.5	04995	3.5	3.3	2E1	4.50		.04	1.59	4.00				3	36	40				
250.5	255.5	04996	5.0	4.1	2E1	3.70		2.91	.51	80.00				5	20	26				
255.5	259.5	04997	4.0	3.8	2E1	4.30		.04	1.11	4.00				2	36	39				
259.5	264.3	04998	4.8	4.5	2E1	4.20		.55	1.38	6.00				3	33	37				
264.3	271.0	04999	6.7	6.6	2E4	4.50		5.81	8.21	16.00				6	27	34				
271.0	275.0	05000	4.0	3.6	2E1	4.20		.31	1.59	6.00				4	31	36				
275.0	279.0	43051	4.0	3.3	2E1	4.10		.79	.71	10.00				4	31	36				
279.0	283.0	43052	4.0	3.1	2E1	4.00		.75	1.18	6.00				3	31	34				
283.0	287.0	43053	4.0	3.0	2E1	4.10		.69	2.55	4.00				5	31	36				
287.0	291.0	43054	4.0	3.3	2E48	4.30		4.35	8.09	12.00				4	28	33				
291.0	295.0	43055	4.0	3.8	2E48	4.20		2.88	6.31	10.00				4	29	33				
295.0	299.0	43056	4.0	3.7	2E48	4.50		4.02	8.37	10.00				6	24	31				
299.0	302.0	43057	3.0	2.2	2E48	4.20		1.45	4.23	6.00				6	29	36				
302.0	306.5	43058	4.5	3.8	2E08	4.50		1.09	2.20	6.00				5	34	40				
306.5	311.0	43059	4.5	4.2	2E08	4.20		1.14	1.93	8.00				6	30	37				
311.0	315.0	43060	4.0	2.8	2E08	4.40		.65	1.71	8.00				7	32	39				
315.0	319.5	43061	4.5	3.9	2E08	4.40		.87	1.80	8.00				6	33	40				
319.5	324.0	43062	4.5	4.2	2E08	4.20		.22	1.14	6.00				7	29	36				
324.0	327.0	43063	3.0	.9	BXA	2.90		.14	.47	8.00				6	6	12				
327.0	331.5	43064	4.5	4.1	2E4	4.80		4.49	8.39	20.00				1	35	36				
331.5	335.5	43065	4.0	3.7	2E0	4.40		5.02	9.28	26.00				2	29	31				
335.5	339.5	43066	4.0	3.9	2A34	4.50		5.21	10.30	26.00				1	29	31				
339.5	344.0	43067	4.5	4.1	2A34	3.70		3.86	9.52	24.00				2	19	21				
344.0	348.8	43068	4.8	4.4	2A34	3.50		1.40	5.76	20.00				2	18	21				
348.8	351.5	43069	2.7	2.4	2A34	3.50		4.87	10.10	26.00				3	11	15				
351.5	355.0	43070	3.5	3.2	2A34	4.10		3.91	9.45	20.00				2	24	27				
355.0	359.3	43071	4.3	4.0	2A34	3.50		2.23	6.50	14.00				1	17	19				
359.3	363.5	43072	4.2	3.9	2A34	3.40		4.32	12.80	24.00				2	11	13				
363.5	367.0	43073	3.5	3.5	2J732	3.90		8.27	20.70	34.00				10	8	18				
367.0	373.0	43074	6.0	5.1	2D5	3.10		1.54	5.29	16.00				5	8	13				

DDH: 86F-25 UTM-N: 8979.0 UTM-E: 14772.6 UTM-ELEV: 3713.0 TOTAL DEPTH: 411.0 SECTION: 121+000
 RFE: S2 RFE DIR: 235 PLUNGE ANGLES: 0 315 DHD CALC: 1 SS CALC: 1

-----DEPTHS-----							-----ASSAYS-----														
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	Cu %	Pb %	Zn %	Ag(AA) g/mT	Ag(FA) g/mT	Au(FA) g/mT	Po %	Py %	TOT Fe	BaO %	Hg %	Mn %	As %	Ba %	S.G. W.R.
167.5	170.0	10694	2.5	2.4	2D0	3.10		2.02	3.39	36.00				5	9	15					
170.0	175.5	10695	5.5	3.3	1D4	2.80		.47	.27	10.00				2	2	5					
175.5	181.0	10696	5.5	3.1	2LE34	3.70		4.31	3.97	74.00				11	15	26					
181.0	185.0	10697	4.0	1.7	2LE34	4.30		5.30	4.95	84.00				14	21	36					
185.0	189.7	10698	4.7	2.4	2LE34	3.50		2.97	2.38	44.00				8	17	25					
189.7	195.7	10699	6.0	5.9	2G4	4.10		5.00	5.01	72.00				2	21	23					
195.7	200.0	10700	4.3	4.1	2E4L	3.60		.87	1.01	30.00				5	23	28					
200.0	207.8	10701	7.8	7.4	1H4	2.90		.72	.31	38.00				7	4	12					
207.8	212.5	10702	4.7	4.4	2E0	4.10		2.44	1.23	32.00				1	36	38					
212.5	217.6	10703	5.1	5.0	2E4	4.60		1.69	2.40	22.00				1	38	40					
217.6	221.6	10704	4.0	3.7	2E4	4.70		2.57	3.91	22.00					41	42					
221.6	226.0	10705	4.4	3.9	2E4	4.30		4.78	3.40	28.00				1	30	32					
226.0	232.5	10706	6.5	5.7	2E4	4.60		3.17	3.17	32.00				4	36	40					
232.5	239.8	10707	7.3	6.8	2C3	4.00		2.18	.17	34.00					33	33					
239.8	244.6	10708	4.8	4.7	2E0	4.60		1.54	.86	24.00				2	40	42					
244.6	250.7	10709	6.1	5.9	2E0	4.80		1.47	.75	20.00				1	39	41					
250.7	258.0	10710	7.3	6.9	2E84	4.60		2.93	2.30	44.00				4	36	40					
258.0	264.0	10711	6.0	5.8	2E84	4.50		3.15	3.95	36.00				5	32	38					
264.0	268.8	10712	4.8	4.4	2E8	4.40		1.14	2.78	14.00				7	31	39					
268.8	273.0	10713	4.2	3.5	2E0	4.40		.92	1.12	8.00				1	38	39					
273.0	278.0	10714	5.0	4.8	2E4	4.80		5.35	8.18	44.00				1	36	37					
278.0	282.0	10715	4.0	4.0	2E0	4.50		.13	.14	6.00					39	40					
282.0	286.7	10716	4.7	2.1	2E0	4.50		2.06	1.88	16.00				1	37	39					
286.7	290.0	10717	3.3	2.3	2E8	4.50		1.63	1.95	14.00				6	34	41					
290.0	295.0	10718	5.0	4.2	2E8	4.00		1.46	2.12	12.00				2	31	34					
295.0	299.0	10719	4.0	3.9	2E84	4.50		2.35	5.33	16.00				6	32	39					
299.0	303.0	10720	4.0	3.8	2E8	4.60		.55	.66	6.00				6	37	44					
303.0	306.5	10721	3.5	2.2	2E8	4.60		1.45	2.24	12.00				8	33	41					
306.5	310.0	10722	3.5	3.2	2E4	4.60		2.10	3.00	24.00				5	35	41					
310.0	315.0	10723	5.0	3.9	2E4	4.70		3.00	6.15	20.00				4	33	37					
315.0	319.0	10724	4.0	3.4	2E4	4.50		2.70	5.38	20.00				1	36	38					
319.0	324.0	10725	5.0	3.6	2E4	4.80		3.46	5.21	20.00					37	38					
324.0	330.0	10726	6.0	3.7	2E4	4.70		2.00	3.48	14.00				1	40	41					
330.0	335.0	10727	5.0	4.1	2E4	4.60		4.90	9.35	22.00				1	33	35					
335.0	339.0	10728	4.0	3.7	2E4	4.60		3.45	6.85	16.00				2	32	34					
339.0	343.5	10729	4.5	4.2	2E4	4.40		4.16	8.59	20.00				2	32	35					
343.5	348.0	10730	4.5	2.3	2C5	3.30		1.27	1.87	18.00				6	13	20					
348.0	355.0	10731	7.0	6.8	2C5	3.00		1.25	2.73	24.00				2	4	6					
355.0	361.3	10732	6.3	5.8	2D5	3.00		2.11	2.06	32.00				2	2	4					
361.3	364.0	10733	2.7	2.6	2C05	3.30		.25	.43	8.00				10	13	24					
364.0	367.0	10734	3.0	2.9	2D75	3.60		1.63	4.34	24.00				13	15	28					
367.0	374.0	10735	7.0	6.8	2C5	3.10		.40	2.09	10.00				3	11	15					
374.0	378.5	10736	4.5	4.5	2C0	2.80		.68	1.44	16.00				1	4	6					
378.5	383.0	10737	4.5	4.4	2C0	2.90		.81	2.12	16.00				3	3	7					

**THIS REPORT WAS REQUESTED BY: LEEP .GEOLOGY AT: 23:20:10