

WHITEHORSE ASSAY OFFICE

Box 4518

WHITEHORSE, YUKON

017491

Samples From: Anvil Mining Corporation

Lot. No.: A-599-78

P.O. # 31933

Geochem. & Wet Analysis

Rock Type	Sample #	Cu	Pb	Zn
Calc. Phyll.	28	28	8	72
	34	28	20	32
	35	84	4	56
	38-A	48	28	24
	39-A	16	16	16
	40-A	28	4	32
	38-B	24	4	8
	39-B	36	8	40
	40-B	24	12	72
	Q-48	32	16	64
	Q-52	8	36	8
	Q-63	12	20	32
	Q-51-A	24	12	152
	Q-51-B	8	20	8
BMP	29	24	4	136
	Q-47	20	12	16
BMS	30	20	4	48
	F-4-A	24	20	120
GP	31	56	16	96
	32	24	4	104
	44	32	8	96
	45	20	4	48
	50	16	Tr.	Tr.
	33-A	24	4	64
	42-A	32	4	8
	49-A	32	4	96
	33-B	40	16	88
	42-B	24	12	40
	49-B	32	8	104
	Q-45	52	16	24
	Q-46	80	16	152
	Q-50	16	12	72
	Q-56	16	16	88
	Q-57	32	16	104
	Q-58	32	20	168
	Q-44-B	20	12	8
	F-16	68	20	96
	F-1-A	52	20	48
	F-17-A	20	24	32

Rock Type	Sample #	Cu	Pb	Zn
GP	F-1-B	40	16	96
	F-17-B	12	20	72
	F-1-C	36	8	80
CS	37	4	32	32
	27-A	40	24	24
	41-A	32	12	16
	47-A	20	12	32
	27-B	16	12	40
	41-B	20	18	16
	47-B	72	20	136
	27-C	64	24	240
	Q-35-A	40	16	24
	Q-35-C	32	20	16
	Mass. Py. Qtzite.	Q-11	16	780
Carb. Marb.	Q-60	12	28	16
Sericite Phyllite	Q-44-A	8	8	8
QFB-Py in CS	Q-35-B	16	520	32
Mass Py	Q-44-C	36	100	16
	Q-44-D	28	76	16
"Rhyolite"	F-4-B	36	20	104
	F-4-C	48	32	48

WHITEHORSE ASSAY OFFICE
 BOX ~~4318~~ 4318
 WHITEHORSE, YUKON

Samples from: ANVIL MINING CORPORATION
P.O. # 31933

Lot. No.: A-599-78
GEOCHEM. & WET ANALY.

SAMPLE #	Cu	Pb	Zn	SAMPLE #	Cu	Pb	Zn
28 Calc. phyll	28	8	72	Q-60	12	28	16
29 BMP	24	4	136	Q-63	12	20	32
30 BMS	20	4	48	Q-35-A	40	16	24
31 GP	56	16	96	Q-44-A	8	8	8
32 GP	24	4	104	Q-51-A	24	12	152
34 Calc. phyll	28	20	32	Q-35-B	16	520	32
35 Calc. phyll	84	4	56	Q-44-B	20	12	8
37 CS	4	32	32	Q-51-B	8	20	8
44 GP	32	8	96	Q-35-C	32	20	16
45 GP	20	4	48	Q-44-C	36	100	16
50 GP	16	TR	TR	Q-44-D	28	76	16
27-A CS	40	24	24	F-16	68	20	96
33-A GP	24	4	64	F-1-A	52	20	48
38-A Calc. Phyll	48	28	24	F-4-A	24	20	120
39-A Calc. Phyll	16	16	16	F-17-A	20	24	32
40-A Calc. Phyll	28	4	32	F-1-B	40	16	96
41-A CS	32	12	16	F-4-B	36	20	104
42-A GP	32	4	8	F-17-B	12	20	72
47-A CS	20	12	32	F-1-C	36	8	80
49-A GP	32	4	96	F-4-C	48	32	48
27-B CS	16	12	40	F-4-D	420	1380	5.61%
33-B GP	40	16	88	F-4-E H.G.	10,320	1940	1.84%
38-B Calc. phyll	24	4	8	W-15-A	1960	3.46%	8.23%
39-B Calc. phyll	36	8	40	W-15-B	1160	41.7%	11.2%
40-B Calc. phyll	24	12	72	W-15-C	46	196	236
41-B CS	20	18	16	W-15-D	104	44	256
42-B GP	24	12	40	W-15-E	376	3600	12.54%
47-B CS	72	20	136	70-D-1 105'	32	36	136
49-B GP	32	8	104	180'	80	20	304
27-C CS	64	24	240	192'	84	8	360
Q-11 ^{mass. py.} Quartz	16	780	56	217'	72	8	128
Q-45 GP	52	16	24	230'	56	8	120
Q-46 GP	80	16	152	311'	84	8	80
Q-47 BMP	20	12	16	338.5'	72	8	72
Q-48 Calc. phyll	32	16	64	430'	88	8	64
Q-50 GP	16	12	72	451'	40	8	64
Q-52 Calc. phyll	8	36	8	520'	20	20	48
Q-56 GP	16	16	88	562'	48	16	88
Q-57 GP	32	16	104				
Q-58 GP	32	20	168				

UNLESS DENOTED BY % SIGN
 INDICATING WET ANALYSIS, ALL
 RESULTS REPORTED IN P.P.M.

Date: January 22/74

Assayer: K. Hoyland

WHITEHORSE ASSAY OFFICE
 BOX 4518
 WHITEHORSE, YUKON

Samples from: ANVIL MINING CORPORATION
P.O. # 31933

Lot. No.: A-599-78
GEOCHEM. + WET ANALY.

SAMPLE #	Cu	Pb	Zn	SAMPLE #	Cu	Pb	Zn
28	28	8	72	Q-60	12	28	16
29	24	4	136	Q-63	12	20	32
30	20	4	48	Q-35-A	40	16	24
31	56	16	96	Q-44-A	8	8	8
32	24	4	104	Q-51-A	24	12	152
34	28	20	32	Q-35-B	16	520	32
35	84	4	56	Q-44-B	20	12	8
37	4	32	32	Q-51-B	8	20	8
44	32	8	96	Q-35-C	32	20	16
45	20	4	48	Q-44-C	36	100	16
50	16	TR	TR	Q-44-D	28	76	16
27-A	40	24	24	F-16	68	20	96
33-A	24	4	64	F-1-A	52	20	48
38-A	48	28	24	F-4-A	24	20	120
39-A	16	16	16	F-17-A	20	24	32
40-A	28	4	32	F-1-B	40	16	96
41-A	32	12	16	F-4-B	36	20	104
42-A	32	4	8	F-17-B	12	20	72
47-A	20	12	32	F-1-C	36	8	80
49-A	32	4	96	F-4-C	48	32	48
27-B	16	12	40	F-4-D	420	1380	5.61%
33-B	40	16	88	F-4-E H.G.	10,320	1940	1.84%
38-B	24	4	8	W-15-A	1960	3.46%	8.23%
39-B	36	8	40	W-15-B	1160	41.7%	11.2%
40-B	24	12	72	W-15-C	46	196	256
41-B	20	18	16	W-15-D	104	44	256
42-B	24	12	40	W-15-E	376	3600	12.54%
47-B	72	20	136	70-D-1 105'	32	36	136
49-B	32	8	104	180'	80	20	304
27-C	64	24	240	192'	84	8	360
Q-11	16	780	56	217'	72	8	128
Q-45	52	16	24	230'	56	8	120
Q-46	80	16	152	311'	84	8	80
Q-47	20	12	16	338.5'	72	8	72
Q-48	32	16	64	430'	88	8	64
Q-50	16	12	72	451'	40	8	64
Q-52	8	36	8	520'	20	20	48
Q-56	16	16	88	562'	48	16	88
Q-57	32	16	104				
Q-58	32	20	168				

UNLESS DENOTED BY % SIGN
 INDICATING WET ANALYSIS, ALL
 RESULTS REPORTED IN R.P.H.

Date: January 22/74

Assayer: K. Hoyland