

DY PROPERTY  
LENGTH WEIGHTED GRADE CALC'S

File: ASSYDAT.WR1

76X21 ELEVATION: 0000

HOLE-ID	FROM (m)	TO (m)	INTERVAL	ROCK CODE	SG-PULP	Pb%	Zn%	Pb+Zn%	Ag(g/t)	Au(g/t)		
76X21	0	513.6		WASTE	-1	-1	-1	-1	-1	-1		
76X21	513.6	515.1	1.5	4K1	-1	0.72	0.13	0.85	9	-1		
76X21	515.1	516.6	1.5	4K1B	-1	1	0.01	1.01	10	-1		
76X21	516.6	517.6	1	4K1B9	-1	0.1	0.01	0.11	7.5	-1		
76X21	517.6	518.5	0.9	4K1B9	-1	0.09	0.01	0.1	6.5	-1		
76X21	518.5	520	1.5	4A0	-1	0.85	2.35	3.2	7.5	-1		
76X21	520	520.8	0.8	4A0	-1	1.43	1.85	3.28	17.4	-1		
76X21	520.8	521.2	0.4	5B6	-1	0.3	0.2	0.5	5.6	-1		
76X21	521.2	563	41.8	WASTE	-1	-1	-1	-1	-1	-1		
76X21	563	564.5	1.5	4E0	-1	0.12	0.04	0.16	2.8	-1		
76X21	564.5	565.5	1	4D9	-1	0.75	0.96	1.71	10	-1		
76X21	565.5	566.3	0.8	4L6	-1	0.04	0.07	0.11	1.9	-1		
76X21	566.3	566.6	0.3	4E0	-1	0.04	0.02	0.06	3.7	-1		
76X21	566.6	567	0.4	4L6	-1	0.02	0.02	0.04	0.3	-1		
76X21	567	568.9	1.9	4K0	-1	0.07	0.02	0.09	3.7	-1		
76X21	568.9	570	1.1	4L6	-1	0.02	0.02	0.04	0.3	-1		
76X21	570	571.4	1.4	4K9	-1	0.24	0.26	0.5	6.5	-1		
76X21	571.4	572.9	1.5	4C79	-1	0.05	0.01	0.06	3.7	0.01		
76X21	572.9	574.4	1.5	4C7	-1	0.03	0.01	0.04	0.9	0.01		
76X21	574.4	575.9	1.5	4C7	-1	0.23	0.6	0.83	4.7	0.01		
76X21	575.9	577.4	1.5	4C7	-1	0.27	0.28	0.55	7.2	0.02		
76X21	577.4	579	1.6	4C7	-1	0.18	0.08	0.26	4.7	0.01		
76X21	579	580.5	1.5	4C7	-1	0.12	0.33	0.45	1.9	0.01		
76X21	580.5	581.7	1.2	4C7	-1	0.05	0.01	0.06	1.9	0.01		
76X21	581.7	582.6	0.9	4E0	4.3	3.31	6.5	9.81	51	0.34	8.829	Pb..... 2.77% /7.8m
76X21	582.6	584.2	1.6	4A4	3.18	2.61	4.19	6.8	48	0.69	10.88	
76X21	584.2	585.7	1.5	4A4	3.12	2.48	4.42	6.9	36	0.41	10.35	Zn..... 4.68% /7.8m
76X21	585.7	587.2	1.5	4A4	3.09	3.25	5.62	8.87	77	1.03	13.305	
76X21	587.2	588	0.8	4A49	3.59	3.39	6.17	9.56	71	0.75	7.648	Pb+Zn.. 7.45% /7.8m
76X21	588	589.5	1.5	4D0	-1	2.1	2.65	4.75	30.2	0.02	7.125	
76X21	589.5	618.1	28.6	WASTE	-1	-1	-1	-1	-1	-1	58.137	7.8 m
76X21	618.1	619.6	1.5	4A0	-1	1.5	2.1	3.6	23	0.02	5.4	
76X21	619.6	621.1	1.5	4A4	-1	1	2.75	3.75	10.9	0.01	5.625	4.10% /4.7m
76X21	621.1	622.8	1.7	4A4	-1	1.25	3.6	4.85	13.7	0.02	8.245	
76X21	622.8	774.9	152.1	WASTE	-1	-1	-1	-1	-1	-1	19.27	4.7 m

017650

DI PROPERTY  
LENGTH WEIGHTED GRADE CALC'S

File: ASSYDAT.WR1

HOLE-ID	FROM (m)	TO (m)	INTERVAL	ROCK CODE	SG-PULP	Pb%	Zn%	Pb+Zn%	Ag(g/t)	Au(g/t)		
77X01	581.4	582.4	1	4E09	3.91	5.09	8.42	13.51	97	1.37	13.51	
77X01	582.4	583.4	1	4E0	4.15	6.2	10.67	16.87	104	0.75	16.87	12.91% /3.3m
77X01	583.4	584.7	1.3	4E15	3.45	3.77	5.64	9.41	58	0.89	12.233	
77X01	584.7	590.2	5.5	WASTE	-1	-1	-1	-1	-1	-1	42.613	3.3 m
77X01	590.2	592.2	2	4C0	-1	0.24	0.37	0.61	0.7	-1		
77X01	592.2	593.5	1.3	4A0	-1	1.33	0.49	1.82	6.5	-1		
77X01	593.5	595.5	2	4C0	-1	1.72	3.98	5.7	28.8	-1	11.4	
77X01	595.5	597.5	2	4C09	-1	1.12	1.19	2.31	15.1	-1	4.62	
77X01	597.5	599.5	2	4C09	-1	1.09	1.82	2.91	17.5	-1	5.82	
77X01	599.5	601	1.5	4D09	-1	1.72	3.57	5.29	28.8	-1	7.935	
77X01	601	603	2	4D5	-1	2	3.51	5.51	33.6	-1	11.02	
77X01	603	605	2	4C5	-1	0.78	2.13	2.91	15.8	-1	5.82	
77X01	605	607	2	4C5	-1	1.59	2.57	4.16	29.1	-1	8.32	
77X01	607	608	1	4D5	-1	3.07	4.36	7.43	50.1	-1	7.43	
77X01	608	609.5	1.5	4D5	-1	2.53	4.51	7.04	39.4	-1	10.56	4.93% /31.7m m
77X01	609.5	611.5	2	4D09	-1	2.29	3.34	5.63	64.1	-1	11.26	
77X01	611.5	613.4	1.9	4K6	-1	1.1	2.52	3.62	28.5	-1	6.878	
77X01	613.4	615.4	2	4C5	-1	1.19	2.52	3.71	26.1	-1	7.42	
77X01	615.4	617.4	2	4C59	-1	1.98	2.69	4.67	30.9	-1	9.34	
77X01	617.4	618.4	1	4D5	-1	3.53	5.15	8.68	56.9	-1	8.68	
77X01	618.4	620	1.6	4C5	-1	1.68	3.11	4.79	24.7	-1	7.664	
77X01	620	620.9	0.9	4G0	-1	0.6	2.59	3.19	12	-1	2.871	
77X01	620.9	622.6	1.7	5B6	-1	0.09	0.48	0.57	0.1	-1	0.969	
77X01	622.6	624	1.4	4L14	2.77	1.79	2.73	4.52	30	1.23	6.328	
77X01	624	625.2	1.2	4G0	4.22	7.15	11.21	18.36	127	0.69	22.032	
77X01	625.2	774.9	149.7	WASTE	-1	-1	-1	-1	-1	-1	156.367	31.7

DY PROPERTY  
 LENGTH WEIGHTED GRADE CALC'S

File: ASSYDAT.WR1

HOLE-ID	FROM (m)	TO (m)	INTERVAL	ROCK CODE	SG-PULF	Pb%	Zn%	Pb+Zn%	Ag(g/t)	Au(g/t)	
77X03	698.1	700.1	2	4L17	-1	0.09	0.11	0.2	0.1	-1	
77X03	700.1	701.1	1	4E84	4.3	9.85	5.11	14.96	127	0.69	14.96
77X03	701.1	702.6	1.5	4E849	4.41	3.68	3.59	7.27	53	0.62	10.905
77X03	702.6	703.6	1	4G184	4.47	5.88	6.99	12.87	77	0.55	12.87
77X03	703.6	704.6	1	4E187	-1	2.46	3.01	5.47	41.2	-1	5.47
77X03	704.6	705.9	1.3	4E187	-1	1.73	3.51	5.24	36.7	-1	6.812
77X03	705.9	707.9	2	4K68	-1	5.02	1.97	6.99	51.1	-1	13.98
77X03	707.9	709.9	2	4K689	-1	1.92	0.96	2.88	28.5	-1	64.997
77X03	709.9	710.8	0.9	4C79	-1	0.57	0.96	1.53	7.2	-1	7.8
77X03	710.8	712.8	2	4A0	-1	0.07	0.24	0.31	1.4	-1	
77X03	712.8	714	1.2	4A0	-1	0.44	0.28	0.72	6.2	-1	
77X03	714	716	2	4G9	-1	3.26	4.05	7.31	54.9	-1	
77X03	716	717.2	1.2	4E89	-1	0.41	0.45	0.86	18.2	-1	
77X03	717.2	719.2	2	4L37	-1	0.01	0.02	0.03	0.1	-1	
77X03	719.2	729.2	10	WASTE	-1	-1	-1	-1	-1	-1	
77X03	729.2	731.2	2	4A0	-1	0.29	0.34	0.63	0.1	-1	
77X03	731.2	733.2	2	4E186	-1	0.52	0.38	0.9	13	-1	
77X03	733.2	735.2	2	4E186	-1	2.32	1.74	4.06	32.9	-1	
77X03	735.2	736.6	1.4	4E186	-1	1.74	1.42	3.16	24.7	-1	
77X03	736.6	737.6	1	4A0	-1	0.51	0.27	0.78	4.1	-1	
77X03	737.6	739.3	1.7	4L37	-1	1.08	0.65	1.73	13	-1	
77X03	739.3	741.3	2	4C7	-1	2.04	1.21	3.25	36.3	-1	
77X03	741.3	742.6	1.3	4G9	-1	1.24	1.44	2.68	28.5	-1	
77X03	742.6	743.6	1	4C75	-1	0.26	0.3	0.56	16.8	-1	
77X03	743.6	745.6	2	4L17	-1	0.04	0.02	0.06	0.1	-1	
77X03	745.6	844.3	98.7	WASTE	-1	-1	-1	-1	-1	-1	

8.33% /7.8m

DY PROPERTY  
LENGTH WEIGHTED GRADE CALC'S

File: ASSYDAT.WR1

HOLE-ID	FROM (m)	TO (m)	INTERVAL	ROCK CODE	SG-PULP	Pb%	Zn%	Pb+Zn%	Ag(g/t)	Au(g/t)		
77X05	590	591	1	4G9	-1	1.69	0.91	2.6	31	-1		
77X05	591	593	2	4G9	3.95	3.98	2.76	6.74	52.8	-1	13.48	
77X05	593	594.3	1.3	4G0	4.68	5.6	5.66	11.26	80	0.69	14.638	
77X05	594.3	595.2	0.9	4E69	4.47	4.36	6.48	10.84	77	0.82	9.756	
77X05	595.2	597.2	2	4G0	4.48	5.51	5.45	10.96	65	0.41	21.92	
77X05	597.2	598.3	1.1	4G9	4.61	4.82	4.34	9.16	60	0.62	10.076	8.27% /17.3m
77X05	598.3	600.3	2	4C69	4.45	3.35	1.72	5.07	52.8	-1	10.14	
77X05	600.3	602.3	2	4C69	3.67	2.3	1.76	4.06	36.2	-1	8.12	
77X05	602.3	604.3	2	4G0	4.68	5.89	4.67	10.56	69	0.48	21.12	
77X05	604.3	606.3	2	4G0	4.55	6.35	5.11	11.46	76	0.41	22.92	
77X05	606.3	608.3	2	4C69	3.91	2.95	2.49	5.44	43.4	-1	10.88	
77X05	608.3	609.2	0.9	4L79	-1	1.46	1.47	2.93	28.9	-1	143.05	17.3
77X05	609.2	614.4	5.2	WASTE	-1	-1	-1	-1	-1	-1		
77X05	614.4	615.4	1	4C79	-1	2.33	2.16	4.49	33.1	-1	4.49	
77X05	615.4	617.2	1.8	4C79	-1	3.09	2.84	5.93	39.3	-1	10.674	7.13% /4.1m
77X05	617.2	618.5	1.3	4G0	4.5	6.2	4.61	10.81	75	0.65	14.053	
77X05	618.5	619.1	0.6	WASTE	-1	-1	-1	-1	-1	-1	29.217	4.1
77X05	619.1	621.1	2	4A0	3.16	3.1	4.7	7.8	37	0.45	15.6	
77X05	621.1	622.4	1.3	4A0	3.02	1.79	3.62	5.41	20	0.27	7.033	
77X05	622.4	624.1	1.7	4E9	4.49	5.05	4.4	9.45	67	0.41	16.065	7.49% /8.7m
77X05	624.1	626.3	2.2	4A0	3.06	2.25	3.85	6.1	27	0.27	13.42	
77X05	626.3	627.8	1.5	4E469	4.51	4.76	3.93	8.69	57	0.55	13.035	
77X05	627.8	635.5	7.7	WASTE	-1	-1	-1	-1	-1	-1	65.153	8.7
77X05	635.5	636.7	1.2	4H19	-1	3.56	3.25	6.81	61.7	-1		
77X05	636.7	640.5	3.8	WASTE	-1	-1	-1	-1	-1	-1		
77X05	640.5	642.9	2.4	4C7	-1	0.15	1.64	1.79	3	-1		
77X05	642.9	671.5	28.6	WASTE	-1	-1	-1	-1	-1	-1		
77X05	671.5	673.2	1.7	4E89	-1	0.85	0.91	1.76	16	-1		
77X05	673.2	673.6	0.4	WASTE	-1	-1	-1	-1	-1	-1		
77X05	673.6	675	1.4	4E89	-1	1.47	1.76	3.23	23.8	-1		
77X05	675	707.7	32.7	WASTE	-1	-1	-1	-1	-1	-1		
77X05	707.7	709	1.3	4C79	-1	0.29	0.32	0.61	6	-1		
77X05	709	711	2	4G19	4.26	5.15	7.13	12.28	98	1.37	24.56	
77X05	711	713	2	4G19	4.54	6.05	8.67	14.72	123	1.65	29.44	12.93% /7.0m
77X05	713	715	2	4G19	4.45	5.33	7.85	13.18	116	1.37	26.36	
77X05	715	716	1	4A0	3.39	3.83	6.31	10.14	84	0.69	10.14	
77X05	716	740.2	24.2	WASTE	-1	-1	-1	-1	-1	-1	90.5	7
77X05	740.2	742.4	2.2	4E89	4.33	4.52	5.48	10	85	1.03		
77X05	742.4	762.3	19.9	WASTE	-1	-1	-1	-1	-1	-1		
77X05	762.3	763.5	1.2	4A0	4.26	0.11	1.34	1.45	18.3	-1		



BY PROPERTY  
LENGTH WEIGHTED GRADE CALC'S

File: ASSYDAT.WR1

HOLE-ID	FROM (m)	TO (m)	INTERVAL	ROCK CODE	SG-PULP	Pb%	Zn%	Pb+Zn%	Ag(g/t)	Au(g/t)		
77X06	435.9	436.6	0.7	4E49	-1	1.28	1.42	2.7	17	-1		
77X06	436.6	438.5	1.9	WASTE	-1	-1	-1	-1	-1	-1		
77X06	438.5	440.6	2.1	4C09	-1	0.34	0.36	0.7	10	-1		
77X06	440.6	442.8	2.2	4C09	-1	0.44	0.74	1.18	13	-1		
77X06	442.8	443.2	0.4	WASTE	-1	-1	-1	-1	-1	-1		
77X06	443.2	444.7	1.5	4C49	-1	0.22	0.26	0.48	10	-1		
77X06	444.7	452.6	7.9	WASTE	-1	-1	-1	-1	-1	-1		
77X06	452.6	455.5	2.9	4C0	-1	0.03	0.02	0.05	2	-1		
77X06	455.5	457.5	2	4K09	-1	0.05	0.01	0.06	7	-1		
77X06	457.5	459.5	2	4K09	-1	0.05	0.01	0.06	8	-1		
77X06	459.5	461.5	2	4K09	-1	0.04	0.01	0.05	9	-1		
77X06	461.5	462.7	1.2	4K0	-1	0.28	0.36	0.64	4	-1		
77X06	462.7	541.3	78.6	WASTE	-1	-1	-1	-1	-1	-1		
77X06	541.3	543.3	2	4A14	3.11	1.61	2.89	4.5	44	-1		
77X06	543.3	545.3	2	4A14	2.9	1.98	2.88	4.86	43	-1		
77X06	545.3	547.3	2	4A14	2.99	2.98	4.79	7.77	60	-1	15.54	
77X06	547.3	549.3	2	4A14	2.75	2.51	4.83	7.34	46	-1	14.68	
77X06	549.3	550.8	1.5	4A14	2.76	2.31	4.01	6.32	35	-1	9.48	7.78% /7.0m
77X06	550.8	552.3	1.5	4A14	2.93	3.34	6.48	9.82	75	-1	14.73	
77X06	552.3	557.1	4.8	WASTE	-1	-1	-1	-1	-1	-1	54.43	7
77X06	557.1	559.1	2	4A14	2.78	1.98	3.48	5.46	35	-1		
77X06	559.1	561.1	2	4A14	2.88	1.34	2.67	4.01	27	-1		
77X06	561.1	576.6	15.5	WASTE	-1	-1	-1	-1	-1	-1		
77X06	576.6	578.1	1.5	4A4	3.27	4.43	10.76	15.19	82	0.34	22.785	
77X06	578.1	579.5	1.4	4A4	2.97	2.52	5.53	8.05	48	0.1	11.27	11.74% /2.9m
77X06	579.5	583.7	4.2	WASTE	-1	-1	-1	-1	-1	-1	34.055	2.9
77X06	583.7	584.7	1	4C0	2.99	2.19	4.79	6.98	40	-1	6.98	
77X06	584.7	586.5	1.8	4C0	2.67	1.96	2.84	4.8	36	-1	8.64	
77X06	586.5	588.4	1.9	4E1	3.69	8.23	8.24	16.47	121	0.69	31.293	
77X06	588.4	590.4	2	4G0	4.24	7.11	13.72	20.83	145	0.75	41.66	
77X06	590.4	592.4	2	4G0	3.94	4.76	11.15	15.91	78	0.55	31.82	
77X06	592.4	593.4	1	4G0	4.42	1.61	4.8	6.41	18	0.34	6.41	
77X06	593.4	594.8	1.4	4E1	4.04	10.4	18.99	29.48	240	0.93	41.272	
77X06	594.8	596.8	2	4A4	3.51	10.4	21.33	31.74	182	0.62	63.48	16.73% /28.4m
77X06	596.8	597.7	0.9	4A4	3.55	8.76	21.2	29.96	181	0.75	26.964	
77X06	597.7	599.3	1.6	4G1	3.94	3.96	6.05	10.01	66	0.55	16.016	
77X06	599.3	601.3	2	4G1	3.6	4.11	11.99	16.1	80	0.48	32.2	
77X06	601.3	603.3	2	4G1	3.82	3.75	9.33	13.08	73	0.34	26.16	
77X06	603.3	604.6	1.3	4G1	3.82	7.81	14.23	22.04	151	0.34	28.652	
77X06	604.6	606.6	2	4D6	3.48	6.12	7.01	13.13	98	1.03	26.26	
77X06	606.6	608.5	1.9	4D6	3.43	6.22	10.96	17.18	98	0.69	32.642	
77X06	608.5	610.5	2	4D0	2.9	5.82	8.59	14.41	101	0.55	28.82	
77X06	610.5	612.1	1.6	4E6	3.67	6.74	9.42	16.16	88	0.62	25.856	
77X06	612.1	801	188.9	WASTE	-1	-1	-1	-1	-1	-1	475.125	28.4

DY PROPERTY  
 LENGTH WEIGHTED GRADE CALC'S

File: ASSYDAT.WR1

HOLE-ID	FROM (m)	TO (m)	INTERVAL	ROCK CODE	SG-PULP	Pb%	Zn%	Pb+Zn%	Ag(g/t)	Au(g/t)
77X08	377.6	378	0.4	4A0	-1	0.55	2.56	3.11	10	-1
77X08	378	378.4	0.4	4L0	-1	0.06	0.18	0.24	1	-1
77X08	378.4	379	0.6	4A0	-1	0.57	2.66	3.23	9	-1
77X08	379	379.6	0.6	4L0	-1	0.12	0.43	0.55	0.1	-1
77X08	379.6	991.2	611.6	WASTE	-1	-1	-1	-1	-1	-1

8213  
 149 →  
 914 - 14 → 821

DY PROPERTY  
LENGTH WEIGHTED GRADE CALC'S

File: ASSYDAT.WR1

HOLE-ID	FROM (m)	TO (m)	INTERVAL	ROCK CODE	SG-PULF	Pb%	Zn%	Pb+Zn%	Ag(g/t)	Au(g/t)		
77X09	625.5	627.5	2	4A4	3.12	3.52	8.17	11.69	25	0.72	23.38	
77X09	627.5	629.5	2	4A4	3.06	2.51	4.86	7.37	41	0.27	14.74	
77X09	629.5	631.5	2	4A4	2.91	2.58	4.96	7.54	53	0.14	15.08	
77X09	631.5	633.5	2	4A4	2.96	2.57	5.71	8.28	45	0.69	16.56	7.64% /14.0m
77X09	633.5	635.5	2	4A4	-1	2.63	3.79	6.42	37.7	-1	12.84	
77X09	635.5	637.5	2	4A4	-1	1.74	4.31	6.05	31.1	-1	12.1	
77X09	637.5	639.5	2	4A4	-1	2.18	3.92	6.1	31.9	-1	12.2	
77X09	639.5	639.6	0.1	WASTE	-1	-1	-1	-1	-1	-1	106.9	14
77X09	639.6	641.5	1.9	4A4	-1	2.11	4.09	6.2	31.7	-1	11.78	
77X09	641.5	643.5	2	4A4	-1	1.93	3.86	5.79	31.2	-1	11.58	
77X09	643.5	645.5	2	4A4	-1	1.79	4.18	5.97	27.9	-1	11.94	
77X09	645.5	647.5	2	4A4	-1	1.81	3.86	5.67	30	-1	11.34	6.04% /11.9m
77X09	647.5	649.5	2	4A4	-1	1.88	4.34	6.22	31.1	-1	12.44	
77X09	649.5	651.5	2	4A4	-1	2.58	3.84	6.42	42	-1	12.84	
77X09	651.5	653.5	2	4A0	-1	0.8	1.27	2.07	12.9	-1	71.92	11.9
77X09	653.5	655.5	2	4A0	-1	0.98	1.41	2.39	16.4	-1		
77X09	655.5	657.5	2	4A0	-1	1.34	1.92	3.26	20.9	-1		
77X09	657.5	657.7	0.2	WASTE	-1	-1	-1	-1	-1	-1		
77X09	657.7	659.2	1.5	4A0	-1	1.34	2.33	3.67	21.2	-1		
77X09	659.2	695.7	36.5	WASTE	-1	-1	-1	-1	-1	-1		
77X09	695.7	697.8	2.1	4A7	-1	1.11	1.98	3.09	19.6	-1	6.489	
77X09	697.8	699.6	1.8	4A7	-1	1.61	3.22	4.83	26.9	-1	8.694	
77X09	699.6	701.6	2	4A0	-1	2.69	4.33	7.02	54	-1	14.04	
77X09	701.6	703.2	1.6	4C4	-1	1.81	2.5	4.31	29.8	-1	6.896	7.62% /10.3m
77X09	703.2	704.8	1.6	4D0	3.63	5.6	6.81	12.41	80	1.51	19.856	
77X09	704.8	706	1.2	4H1	3.9	7.14	11.6	18.74	123	0.72	22.488	
77X09	706	802.8	96.8	WASTE	-1	-1	-1	-1	-1	-1	78.463	10.3
77X09	802.8	804.8	2	4L7	-1	0.48	0.42	0.9	5.8	-1		
77X09	804.8	806.8	2	4L7	-1	0.66	0.92	1.58	6.7	-1		
77X09	806.8	809	2.2	4L7	-1	0.3	2.48	2.78	4.5	-1		
77X09	809	836	27	WASTE	-1	-1	-1	-1	-1	-1		

633 = 9.89%  
6.42

DY PROPERTY  
LENGTH WEIGHTED GRADE CALC'S

File: ASSYDAT.WR1

HOLE-ID	FROM (m)	TO (m)	INTERVAL	ROCK CODE	SG-PULP	Pb%	Zn%	Pb+Zn%	Ag(g/t)	Au(g/t)
77X11	549.7	551.3	1.6	4H1	-1	3.04	4.34	7.38	39.4	-1
77X11	551.3	551.5	0.2	WASTE	-1	-1	-1	-1	-1	-1
77X11	551.5	552.8	1.3	4E7	4.23	6.19	8.49	14.68	75	0.75
77X11	552.8	553.2	0.4	WASTE	-1	-1	-1	-1	-1	-1
77X11	553.2	554.8	1.6	4E7	4.06	5.15	6.36	11.51	63	0.75
77X11	554.8	557.1	2.3	4L0	-1	0.52	0.54	1.06	9.4	-1
77X11	557.1	558.2	1.1	4G7	-1	3.42	3.88	7.3	44.5	-1
77X11	558.2	558.8	0.6	WASTE	-1	-1	-1	-1	-1	-1
77X11	558.8	560.3	1.5	4C7	-1	1.06	1.72	2.78	15.5	-1
77X11	560.3	560.7	0.4	WASTE	-1	-1	-1	-1	-1	-1
77X11	560.7	561.7	1	4A9	-1	1.72	2.2	3.92	22.2	-1
77X11	561.7	563.7	2	4E69	-1	2.24	1.36	3.6	42.6	-1
77X11	563.7	565.1	1.4	4A4-	-1	2.12	3.1	5.22	30.4	-1
77X11	565.1	566.5	1.4	4C0	-1	0.58	1.02	1.6	11.8	-1
77X11	566.5	567.9	1.4	4C0	-1	1.24	1.14	2.38	17.8	-1
77X11	567.9	568.3	0.4	WASTE	-1	-1	-1	-1	-1	-1
77X11	568.3	570	1.7	4A0	-1	1	1.16	2.16	17	-1
77X11	570	570.3	0.3	WASTE	-1	-1	-1	-1	-1	-1
77X11	570.3	571.6	1.3	4A0	-1	0.9	0.86	1.76	14.3	-1
77X11	571.6	572.9	1.3	5B6	-1	0.14	0.03	0.17	4.9	-1
77X11	572.9	574	1.1	4A0	-1	0.28	0.08	0.36	7.5	-1
77X11	574	576	2	5B6	-1	0.28	0.2	0.48	6	-1
77X11	576	577	1	5B6	-1	0.72	0.13	0.85	13	-1
77X11	577	578.5	1.5	5B6	-1	0.54	0.2	0.74	9.2	-1
77X11	578.5	580.5	2	4A0	-1	1.56	1.96	3.52	20.2	-1
77X11	580.5	582.3	1.8	4A0	-1	1.48	2.25	3.73	20.1	-1
77X11	582.3	584.3	2	4L0	-1	0.12	0.2	0.32	3	-1
77X11	584.3	660.5	76.2	WASTE	-1	-1	-1	-1	-1	-1
77X11	660.5	661.5	1	4C7	-1	0.23	0.13	0.36	5	-1
77X11	661.5	662.8	1.3	4C7	-1	0.25	0.08	0.33	8.8	-1
77X11	662.8	664.5	1.7	4E1	-1	0.21	0.07	0.28	16.4	-1
77X11	664.5	665.9	1.4	4E8	-1	0.32	0.07	0.39	13.8	-1
77X11	665.9	667.8	1.9	4G89	-1	4.69	3.73	8.42	52.5	-1
77X11	667.8	669.3	1.5	4G19	-1	1.15	1.06	2.21	21.2	-1
77X11	669.3	670.6	1.3	4G89	-1	3.71	1.44	5.15	41.7	-1
77X11	670.6	672.5	1.9	4G9	-1	1.94	0.87	2.81	35.4	-1
77X11	672.5	673.8	1.3	WASTE	-1	-1	-1	-1	-1	-1
77X11	673.8	675.7	1.9	4E16	-1	1.98	1.33	3.31	31.7	-1
77X11	675.7	676.7	1	4G9	-1	0.81	0.28	1.09	22.5	-1
77X11	676.7	678.1	1.4	4E19	-1	0.61	0.39	1	23	-1
77X11	678.1	678.6	0.5	WASTE	-1	-1	-1	-1	-1	-1
77X11	678.6	679.6	1	4E16	-1	1.59	2.25	3.84	22.8	-1
77X11	679.6	681.6	2	4A0	-1	0.89	1.52	2.41	11.8	-1
77X11	681.6	683.3	1.7	4A0	-1	1.32	1.76	3.08	19.8	-1
77X11	683.3	688.1	4.8	WASTE	-1	-1	-1	-1	-1	-1
77X11	688.1	690.1	2	4A0	-1	0.78	0.46	1.24	18.8	-1
77X11	690.1	691.1	1	4E19	-1	0.36	0.12	0.48	20.1	-1
77X11	691.1	692.7	1.6	4E1	-1	0.19	0.06	0.25	21.3	-1
77X11	692.7	731.2	38.5	WASTE	-1	-1	-1	-1	-1	-1
77X11	731.2	732.2	1	4E19	-1	0.61	0.35	0.96	18.8	-1
77X11	732.2	769.6	37.4	WASTE	-1	-1	-1	-1	-1	-1
77X11	769.6	771.6	2	4A64	-1	2.77	4.14	6.91	42	-1

13.82

DY PROPERTY  
 LENGTH WEIGHTED GRADE CALC'S

File: ASSYDAT.WR1

77X11	771.6	773.6	2	4A4	-1	1.83	3.82	5.65	29.8	-1	11.3	
77X11	773.6	775.6	2	4A4	-1	2.34	3.84	6.18	34.7	-1	12.36	
77X11	775.6	777.6	2	4A4	-1	2.34	3.87	6.21	34.1	-1	12.42	
77X11	777.6	779.6	2	4A4	-1	2.09	4.44	6.53	30.8	-1	13.06	
77X11	779.6	781.6	2	4A4	-1	1.95	3.26	5.21	22.3	-1	10.42	5.02% /22.1m
77X11	781.6	783.6	2	4A0	-1	1.72	2.62	4.34	21.9	-1	8.68	
77X11	783.6	785.6	2	4A0	-1	1.64	2.52	4.16	21.4	-1	8.32	
77X11	785.6	787.6	2	4A0	-1	1.45	1.87	3.32	23.7	-1	6.64	
77X11	787.6	789.6	2	4A0	-1	1.56	2.46	4.02	23.1	-1	8.04	
77X11	789.6	791.7	2.1	4A0	-1	1.12	1.72	2.84	18.2	-1	5.964	
											-----	
77X11	791.7	913.1	121.4	WASTE	-1	-1	-1	-1	-1	-1	111.024	22.1

DY PROPERTY  
 LENGTH WEIGHTED GRADE CALC'S

File: ASSYDAT.WR1

HOLE-ID	FROM (m)	TO (m)	INTERVAL	ROCK CODE	SG-PULP	Pb%	Zn%	Pb+Zn%	Ag(g/t)	Au(g/t)
77X4	788.6	790.3	1.7	4C7	-1	0.57	0.53	1.1	2.7	-1
77X4	790.3	791.6	1.3	4E9	-1	2.88	3.45	6.33	28.8	-1
77X4	791.6	793.6	2	4C7	-1	0.02	0.01	0.03	0.1	-1
77X4	793.6	799.7	6.1	4E15	3.48	2.37	5.92	8.29	43	0.41
77X4	799.7	850.1	50.4	WASTE	-1	-1	-1	-1	-1	-1

DY PROPERTY  
LENGTH WEIGHTED GRADE CALC'S

File: ASSYDAT.WR1

HOLE-ID	FROM (m)	TO (m)	INTERVAL	ROCK CODE	SG-PULP	Pb%	Zn%	Pb+Zn%	Ag(g/t)	Au(g/t)		
78X01	475.1	476.7	1.6	4E19	-1	0.84	0.28	1.12	18.6	-1		
78X01	476.7	480.4	3.7	WASTE	-1	-1	-1	-1	-1	-1		
78X01	480.4	482.4	2	4C9	-1	2.13	2.29	4.42	35.3	-1		
78X01	482.4	484.4	2	4C0	-1	1.87	2.4	4.27	27.2	-1		
78X01	484.4	485.4	1	4C0	-1	2.04	1.99	4.03	28.9	-1		
78X01	485.4	486.4	1	4L0	-1	0.37	0.4	0.77	7.1	-1		
78X01	486.4	487.7	1.3	4L0	-1	0.73	0.48	1.21	19.6	-1		
78X01	487.7	616.4	128.7	WASTE	-1	-1	-1	-1	-1	-1		
78X01	616.4	618.4	2	4D4	3.23	3.74	7.24	10.98	76	0.62	21.96	
78X01	618.4	620	1.6	4D4	-1	2.05	3.89	5.94	38	0.48	9.504	8.74% /3.6m
78X01	620	622.1	2.1	5D6	-1	0.26	0.38	0.64	5.7	-1	31.464	3.6
78X01	622.1	623.5	1.4	4A0	-1	0.47	1	1.47	10.3	-1		
78X01	623.5	625.5	2	4A0	-1	1.26	2	3.26	27.8	-1		
78X01	625.5	626.6	1.1	4A0	-1	1.22	1.74	2.96	26.5	-1		
78X01	626.6	629.7	3.1	WASTE	-1	-1	-1	-1	-1	-1		
78X01	629.7	631.7	2	4C0	-1	0.75	1.94	2.69	17.1	-1		
78X01	631.7	633.7	2	4C0	-1	2.24	2.69	4.93	36.4	-1	9.86	
78X01	633.7	635.7	2	4D0	3.22	3.83	6.66	10.49	53	1.3	20.98	
78X01	635.7	637.7	2	4D0	2.91	2.65	6.28	8.93	40	0.34	17.86	
78X01	637.7	639.7	2	4D0	3.03	2.78	5.83	8.61	49	0.82	17.22	
78X01	639.7	640.7	1	4C0	-1	0.92	2.17	3.09	14.2	-1	3.09	
78X01	640.7	642.5	1.8	4D0	-1	3.52	4.47	7.99	61.8	-1	14.382	7.72% /10.8m
78X01	642.5	645.5	3	5A1	-1	0.54	1.26	1.8	5.9	-1	83.392	10.8
78X01	645.5	645.8	0.3	WASTE	-1	-1	-1	-1	-1	-1		
78X01	645.8	647.8	2	4A4	3.08	3.87	7.34	11.21	69	0.69	22.42	
78X01	647.8	649.5	1.7	4A4	2.89	3.65	5.9	9.55	51	0.69	16.235	10.45% /3.7m
78X01	649.5	850.1	200.6	WASTE	-1	-1	-1	-1	-1	-1	38.655	3.7

DY PROPERTY  
LENGTH WEIGHTED GRADE CALC'S

File: ASSYDAT.WR1

HOLE-ID	FROM (m)	TO (m)	INTERVAL	ROCK CODE	SG-PULP	Pb%	Zn%	Pb+Zn%	Ag(g/t)	Au(g/t)		
78X02	508.7	510.7	2	4L7	-1	0.32	0.31	0.63	7	-1		
78X02	510.7	512.6	1.9	4L7	-1	0.14	0.09	0.23	6	-1		
78X02	512.6	514.6	2	4E9	-1	0.44	0.27	0.71	18	-1		
78X02	514.6	515.6	1	4E9	-1	0.08	0.03	0.11	11	-1		
78X02	515.6	581	65.4	WASTE	-1	-1	-1	-1	-1	-1		
78X02	581	581.6	0.6	4E4	-1	5.08	12.07	17.15	128	-1		
78X02	581.6	585.6	4	WASTE	-1	-1	-1	-1	-1	-1		
78X02	585.6	586.9	1.3	4A4	-1	2.5	6.39	8.89	49.2	-1	11.557	
78X02	586.9	588.9	2	4A4	-1	2.83	5.56	8.39	47	-1	16.78	
78X02	588.9	589.9	1	4A4	-1	0.07	0.11	0.18	0.4	-1	0.18	
78X02	589.9	591.7	1.8	5A19	-1	3.11	5.86	8.97	53.9	-1	16.146	
78X02	591.7	593.7	2	4A4	-1	1.78	4.11	5.89	22.1	-1	11.78	
78X02	593.7	595.7	2	4A4	-1	2.17	4.45	6.62	11.6	-1	13.24	
78X02	595.7	597.6	1.9	4A4	-1	2.19	3.86	6.05	13.9	-1	11.495	6.76% /12.0m
78X02	597.6	598.6	1	4A0	-1	0.42	0.93	1.35	3.3	-1	81.178	12.0
78X02	598.6	640.5	41.9	WASTE	-1	-1	-1	-1	-1	-1		
78X02	640.5	642.5	2	4A0	-1	2.14	1.49	3.63	37.4	-1		
78X02	642.5	644	1.5	4A0	-1	0.69	0.78	1.47	15.6	-1		
78X02	644	646	2	4C7	-1	0.4	0.71	1.11	22.5	-1		
78X02	646	648	2	4C7	-1	0.88	1.79	2.67	16.5	-1		
78X02	648	650	2	4C7	-1	0.17	0.25	0.42	1.6	-1		
78X02	650	652	2	4C7	-1	0.27	0.52	0.79	3	-1		
78X02	652	653	1	4L17	-1	0.45	0.36	0.81	6.6	-1		
78X02	653	654	1	4A4	-1	3.65	3.14	6.79	53.4	-1	6.79	
78X02	654	655.1	1.1	4A4	-1	2.47	5.82	8.29	47.6	-1	9.119	7.58% /2.1m
78X02	655.1	674.3	19.2	WASTE	-1	-1	-1	-1	-1	-1	15.909	2.1
78X02	674.3	676.3	2	4A4	3.63	5.77	4.39	10.16	69	0.05	20.32	
78X02	676.3	678.3	2	4A4	3.41	6.22	4.2	10.42	74	1.1	20.84	
78X02	678.3	680.3	2	4E4	3.59	4.16	4.35	8.51	67	2.19	17.02	
78X02	680.3	682.3	2	4E4	-1	3.34	2.18	5.52	55	-1	11.04	
78X02	682.3	684.3	2	4E49	-1	1	2.32	3.32	31	-1	6.64	
78X02	684.3	686.3	2	4D5	3.43	3	6.07	9.07	66	1.37	18.14	
78X02	686.3	687.6	1.3	4D5	3.3	4.57	8.72	13.29	77	1.37	17.277	
78X02	687.6	688.6	1	4E1	-1	1.89	2.96	4.85	28	-1	4.85	
78X02	688.6	690.5	1.9	4E1	-1	2.14	4.34	6.48	47.7	-1	12.312	
78X02	690.5	692.5	2	4D0	3.61	4.5	8.11	12.61	83	1.23	25.22	
78X02	692.5	694.5	2	4D0	3.01	3.81	6.07	9.88	62	0.48	19.76	
78X02	694.5	696.5	2	4D0	-1	1.92	2.25	4.17	25.1	-1	8.34	
78X02	696.5	697.5	1	4D0	-1	1.68	2.82	4.5	22.2	-1	4.5	
78X02	697.5	698.9	1.4	4D0	-1	2.22	4.28	6.5	36.1	-1	9.1	
78X02	698.9	700.9	2	4A4	3.07	3.92	6.14	10.06	65	0.69	20.12	
78X02	700.9	702.2	1.3	4A4	3.04	3.34	5.83	9.17	61	0.62	11.921	8.15% /27.9m
78X02	702.2	703.9	1.7	WASTE	-1	-1	-1	-1	-1	-1	227.4	27.9
78X02	703.9	705.4	1.5	4A4	2.97	3.87	6.41	10.28	66	0.62		
78X02	705.4	807.7	102.3	WASTE	-1	-1	-1	-1	-1	-1		

Handwritten notes and signatures, including a large scribble and the number '175.39'.

BY PROPERTY  
LENGTH WEIGHTED GRADE CALC'S

File: ASSYDAT.WR1

DY PROPERTY  
 LENGTH WEIGHTED GRADE CALC'S

File: ASSYDAT.WR1

HOLE-ID	FROM (m)	TO (m)	INTERVAL	ROCK CODE	SG-PULP	Pb%	Zn%	Pb+Zn%	Ag(g/t)	Au(g/t)		
78X04	518.4	520.6	2.2	4G4	4.35	5.38	12.19	17.57	92	0.62		
78X04	520.6	532.3	11.7	WASTE	-1	-1	-1	-1	-1	-1		
78X04	532.3	533.4	1.1	4JO	3.46	4.42	12.45	16.87	49	0.14		
78X04	533.4	533.9	0.5	WASTE	-1	-1	-1	-1	-1	-1		
78X04	533.9	534.5	0.6	4JO	3.97	3.77	10.82	14.59	43	0.07		
78X04	534.5	556.6	22.1	WASTE	-1	-1	-1	-1	-1	-1		
78X04	556.6	558.6	2	4E0	4.4	11.2	15.25	26.53	192	0.89	53.06	
78X04	558.6	560	1.4	4E9	3.82	8.72	13.04	21.76	134	1.58	30.464	
78X04	560	562	2	4E0	4.25	8.23	10.39	18.62	122	1.08	37.24	
											22.36% /5.4m	
78X04	562	675	113	WASTE	-1	-1	-1	-1	-1	-1	120.764	5.4



BY PROPERTY  
 LENGTH WEIGHTED GRADE CALC'S

File: ASSYDAT.WR1

HOLE-ID	FROM (m)	TO (m)	INTERVAL	ROCK CODE	SG-PULP	Pb%	Zn%	Pb+Zn%	Ag(g/t)	Au(g/t)
78X06	495.4	495.9	0.5	4EO	-1	0.32	1.28	1.6	8	-1
78X06	495.9	498.2	2.3	4AO	-1	1.97	3.5	5.47	37	-1
78X06	498.2	876.3	378.1	WASTE	-1	-1	-1	-1	-1	-1

DY PROPERTY  
 LENGTH WEIGHTED GRADE CALC'S

File: ASSYDAT.WR1

HOLE-ID	FROM (m)	TO (m)	INTERVAL	ROCK CODE	SG-PULP	Pb%	Zn%	Pb+Zn%	Ag(g/t)	Au(g/t)
78X07	512.4	513.4	1	4K9	-1	0.66	0.17	0.83	21	-1
78X07	513.4	515.6	2.2	WASTE	-1	-1	-1	-1	-1	-1
78X07	515.6	517.6	2	4K9	-1	0.05	0.02	0.07	8	-1
78X07	517.6	519.6	2	4K9	-1	0.03	0.01	0.04	7	-1
78X07	519.6	521.6	2	4C9	-1	0.02	0.01	0.03	10	-1
78X07	521.6	523.6	2	4C9	-1	0.01	0.01	0.02	7	-1
78X07	523.6	525.6	2	4C9	-1	0.03	0.04	0.07	8	-1
78X07	525.6	527.5	1.9	4C9	-1	0.06	0.34	0.4	10	-1
78X07	527.5	529.4	1.9	4C9	-1	0.05	1.07	1.12	7	-1
78X07	529.4	531.4	2	4C9	-1	0.08	0.17	0.25	9	-1
78X07	531.4	533.6	2.2	4C89	-1	0.05	0.02	0.07	11	-1
78X07	533.6	535.6	2	4C89	-1	0.08	0.03	0.11	10	-1
78X07	535.6	537.6	2	4C89	-1	0.34	0.28	0.62	15	-1
78X07	537.6	539.6	2	4C89	-1	0.67	0.65	1.32	15	-1
78X07	539.6	541.6	2	4C8	-1	0.71	0.54	1.25	13	-1
78X07	541.6	543.6	2	4C89	-1	0.83	0.64	1.47	18	-1
78X07	543.6	545.6	2	4C89	-1	0.08	0.04	0.12	10	-1
78X07	545.6	547.6	2	4C89	-1	1.27	1.04	2.31	28	-1
78X07	547.6	549.6	2	4C89	-1	1.39	0.87	2.26	27	-1
78X07	549.6	550.9	1.3	4C89	-1	1.77	1.23	3	28	-1
78X07	550.9	553.6	2.7	WASTE	-1	-1	-1	-1	-1	-1
78X07	553.6	555.2	1.6	4E189	-1	1.52	0.87	2.39	33	-1
78X07	555.2	557	1.8	4L7	-1	0.52	0.48	1	12	-1
78X07	557	558.9	1.9	4C89	-1	2.04	0.17	2.21	36	-1
78X07	558.9	559.3	0.4	WASTE	-1	-1	-1	-1	-1	-1
78X07	559.3	561.3	2	4E19	-1	0.33	0.09	0.42	22	-1
78X07	561.3	562.6	1.3	4E19	-1	0.23	0.07	0.3	17	-1
78X07	562.6	563.2	0.6	WASTE	-1	-1	-1	-1	-1	-1
78X07	563.2	565.2	2	4E19	-1	0.48	0.15	0.63	18	-1
78X07	565.2	565.4	0.2	WASTE	-1	-1	-1	-1	-1	-1
78X07	565.4	567.4	2	4E89	-1	0.73	1.01	1.74	26	-1
78X07	567.4	569.4	2	4E189	-1	1.05	1.01	2.06	27	-1
78X07	569.4	571.4	2	4D8	3.39	5.49	1.88	7.37	52	0.41
78X07	571.4	573.4	2	4C89	-1	0.69	0.19	0.88	15	-1
78X07	573.4	575.4	2	4C89	-1	0.3	0.45	0.75	15	-1
78X07	575.4	577.4	2	4C0	-1	0.14	0.07	0.21	6	-1
78X07	577.4	579.4	2	4C0	-1	0.71	1.51	2.22	16.2	-1
78X07	579.4	581.4	2	4C0	-1	0.12	0.23	0.35	6	-1
78X07	581.4	583.4	2	4C0	-1	0.23	0.23	0.46	8	-1
78X07	583.4	584.4	1	4A0	-1	0.27	0.3	0.57	6	-1
78X07	584.4	585.8	1.4	4A0	-1	0.64	1.42	2.06	8	-1
78X07	585.8	587.5	1.7	WASTE	-1	-1	-1	-1	-1	-1
78X07	587.5	588.4	0.9	4A7	-1	0.14	0.43	0.57	2	-1
78X07	588.4	590.7	2.3	4A7	-1	0.32	0.81	1.13	6	-1
78X07	590.7	595.3	4.6	WASTE	-1	-1	-1	-1	-1	-1
78X07	595.3	596.4	1.1	4C9	-1	0.31	0.22	0.53	9.1	-1
78X07	596.4	617.5	21.1	WASTE	-1	-1	-1	-1	-1	-1
78X07	617.5	619.2	1.7	4A0	-1	0.23	1.24	1.47	2	-1
78X07	619.2	620.7	1.5	WASTE	-1	-1	-1	-1	-1	-1
78X07	620.7	621.7	1	4C0	-1	0.9	0.05	0.95	10.1	-1
78X07	621.7	623.5	1.8	4C0	-1	0.16	0.07	0.23	9.6	-1
78X07	623.5	627.9	4.4	4A0	-1	0.87	1.43	2.3	10.1	-1
78X07	627.9	629.1	1.2	4A0	-1	0.12	0.24	0.36	2	-1

BY PROPERTY  
LENGTH WEIGHTED GRADE CALC'S

File: ASSYDAT.WR1

78X07	629.1	630.7	1.6	4G0	4.64	4.52	2.54	7.06	70	1.03
78X07	630.7	632.1	1.4	4E9	-1	0.78	0.33	1.11	42.9	-1
78X07	632.1	876.3	244.2	WASTE	-1	-1	-1	-1	-1	-1

DY PROPERTY  
 LENGTH WEIGHTED GRADE CALC'S

File: ASSYDAT.WR1

HOLE-ID	FROM (m)	TO (m)	INTERVAL	ROCK CODE	SG-PULP	Pb%	Zn%	Pb+Zn%	Ag(g/t)	Au(g/t)		
78X08	633.2	634.1	0.9	4E4	4.05	7.83	17.89	25.72	141	0.21	23.148	
78X08	634.1	636	1.9	4E4	3.19	4.27	8.89	13.16	77	1.41	25.004	
78X08	636	636.9	0.9	5A1	3.12	0.37	0.72	1.09	17	0.41	0.981	
78X08	636.9	638.9	2	4A4	3.39	2.8	4.06	6.86	52	0.41	13.72	
78X08	638.9	640.9	2	4A4	-1	2.01	2.37	4.38	38	-1	8.76	
78X08	640.9	642.5	1.6	4A4	-1	2.2	3.69	5.89	42	-1	9.424	8.71% /9.3m
78X08	642.5	876.3	233.8	WASTE	-1	-1	-1	-1	-1	-1	81.037	9.3

DY PROPERTY  
LENGTH WEIGHTED GRADE CALC'S

File: ASSYDAT.WR1

HOLE-ID	FROM (m)	TO (m)	INTERVAL	ROCK CODE	SG-PULP	Pb%	Zn%	Pb+Zn%	Ag(g/t)	Au(g/t)		
78X09	556.3	557.6	1.3	4G4	3.76	3	10.29	13.29	40	0.72	17.277	
78X09	557.6	559	1.4	5B6	3.07	1.71	3.78	5.49	29	0.41	7.686	
78X09	559	560.5	1.5	4G0	4.28	2.1	5.83	7.93	35	0.17	11.895	
78X09	560.5	562.1	1.6	4G0	4.16	3.86	7	10.86	68	1.03	17.376	9.35% / 5.8m
78X09	562.1	575.2	13.1	WASTE	-1	-1	-1	-1	-1	-1	54.234	5.8
78X09	575.2	577.2	2	4D4	3.53	4.45	6.33	10.78	83	1.03	21.56	
78X09	577.2	579.2	2	4D4	3.16	3.94	5.94	9.88	71	1.34	19.76	
78X09	579.2	580.2	1	4D4	3.33	4.5	8.34	12.84	69	0.86	12.84	
78X09	580.2	581.4	1.2	4E4	-1	2.4	3.14	5.54	48	-1	<del>6.446</del>	<del>9.81% / 6.2m</del>
78X09	581.4	583.4	2	WASTE	-1	-1	-1	-1	-1	-1	<del>66.808</del>	<u>6.2</u>
78X09	583.4	584.4	1	4K0	-1	0.62	0.68	1.3	37	-1		
78X09	584.4	585.8	1.4	4K0	-1	0.49	0.2	0.69	21	-1		
78X09	585.8	587.1	1.3	4K4	3.8	2.53	7.73	10.26	63	0.48		
78X09	587.1	684.2	97.1	WASTE	-1	-1	-1	-1	-1	-1		

5.0m / 10,83%

DY PROPERTY  
LENGTH WEIGHTED GRADE CALC'S

File: ASSYDAT.WR1

HOLE-ID	FROM (m)	TO (m)	INTERVAL	ROCK CODE	SG-PULP	Pb%	Zn%	Pb+Zn%	Ag(g/t)	Au(g/t)		
78X11	464.9	467.2	2.3	4E89	-1	1.33	0.96	2.29	27	-1		
78X11	467.2	468.6	1.4	WASTE	-1	-1	-1	-1	-1	-1		
78X11	468.6	470.6	2	4E819	-1	0.69	1	1.69	17	-1		
78X11	470.6	471.8	1.2	4E819	-1	0.32	0.6	0.92	14.5	-1		
78X11	471.8	473.8	2	4E819	-1	0.21	0.19	0.4	14.5	-1		
78X11	473.8	475.8	2	4E819	-1	0.23	0.2	0.43	15	-1		
78X11	475.8	477.8	2	4E819	-1	0.24	0.09	0.33	16	-1		
78X11	477.8	479.4	1.6	4E819	-1	0.16	0.06	0.22	10	-1		
78X11	479.4	550.2	70.8	WASTE	-1	-1	-1	-1	-1	-1		
78X11	550.2	552.2	2	4A4	2.72	2.12	5.22	7.34	37	0.5	14.68	
78X11	552.2	554.1	1.9	4A4	2.74	2.1	5.05	7.15	36	0.58	13.585	
78X11	554.1	556.2	2.1	4A4	2.62	3.56	4.63	8.19	53	0.34	17.199	
78X11	556.2	558.3	2.1	4A0	-1	1.62	1.54	3.16	21	-1	6.636	
78X11	558.3	560.1	1.8	4A0	-1	1.04	2.34	3.38	18	-1	6.084	
78X11	560.1	561.2	1.1	4A0	-1	0.78	2.03	2.81	14.5	-1	3.091	
78X11	561.2	562.3	1.1	4A4	-1	2.31	4.77	7.08	37	-1	7.788	5.71% /12.1m
78X11	562.3	583.1	20.8	WASTE	-1	-1	-1	-1	-1	-1	69.063	12.1
78X11	583.1	584.1	1	4A1	-1	1.27	2.44	3.71	14.5	-1		
78X11	584.1	586.1	2	4A1	-1	1.68	2.59	4.27	20	-1		
78X11	586.1	587.5	1.4	4A14	-1	4.7	5.2	9.9	67	-1		
78X11	587.5	589.5	2	4A0	-1	0.92	1.14	2.06	12	-1		
78X11	589.5	591.5	2	4A0	-1	0.86	1.8	2.66	11	-1		
78X11	591.5	592.5	1	4A0	-1	1.3	3.27	4.57	17	-1		
78X11	592.5	594.2	1.7	4A0	-1	0.64	1.61	2.25	7	-1		
78X11	594.2	607.3	13.1	WASTE	-1	-1	-1	-1	-1	-1		
78X11	607.3	609.3	2	4A0	-1	0.17	0.26	0.43	4	-1		
78X11	609.3	611.3	2	4A0	-1	1.84	3.05	4.89	28	-1		
78X11	611.3	613.3	2	4A0	-1	0.91	0.85	1.76	14.5	-1		
78X11	613.3	615.3	2	4A0	-1	1.74	2.83	4.57	26	-1		
78X11	615.3	617.2	1.9	4A4	2.99	3.41	5.64	9.05	53	0.69	17.195	
78X11	617.2	618.3	1.1	4E0	4.24	7.83	7.45	15.28	142	0.96	16.808	
78X11	618.3	619.6	1.3	4B4	4.02	6.83	14.84	21.67	106	0.69	28.171	
78X11	619.6	621.6	2	4D4	3.15	3.47	5.11	8.58	54	0.62	17.16	
78X11	621.6	623.6	2	4D4	3.15	4.31	7.69	12	76	0.82	24	
78X11	623.6	625.2	1.6	4D4	3.73	4.48	7.05	11.53	69	0.69	18.448	12.30% /9.9m
											121.782	9.9
78X11	625.2	627.2	2	4A0	-1	0.92	2.21	3.13	17	-1	6.26	
78X11	627.2	629.2	2	4A0	-1	1.31	2.82	4.13	21	-1	8.26	
78X11	629.2	631.2	2	4A0	-1	0.92	2.62	3.54	18	-1	7.08	
78X11	631.2	632.2	1	4A0	-1	1.06	2.66	3.72	20	-1	3.72	
78X11	632.2	634.1	1.9	4A0	-1	2.44	4.77	7.21	38	-1	13.699	
78X11	634.1	636	1.9	5A1	-1	0.36	0.76	1.12	5	-1	2.128	
78X11	636	638	2	4A0	-1	2	3.01	5.01	35	-1	10.02	4.00% /12.8m
78X11	638	716.2	78.2	WASTE	-1	-1	-1	-1	-1	-1	51.167	12.8

BY PROPERTY  
LENGTH WEIGHTED GRADE CALC'S

File: ASSYDAT.WR1

HOLE-ID	FROM (m)	TO (m)	INTERVAL	ROCK CODE	SG-PULP	Pb%	Zn%	Pb+Zn%	Ag(g/t)	Au(g/t)		
79X01	509.8	511.4	1.6	4K9	-1	0.06	0.02	0.08	5	-1		
79X01	511.4	512.9	1.5	4K9	-1	0.22	0.1	0.32	6.5	-1		
79X01	512.9	514.9	2	4K0	-1	0.38	0.14	0.52	7	-1		
79X01	514.9	517	2.1	4K0	-1	0.09	0.02	0.11	4	-1		
79X01	517	518.7	1.7	4E0	-1	0.48	0.15	0.63	5	-1		
79X01	518.7	520.7	2	4C9	-1	0.79	0.46	1.25	18	-1		
79X01	520.7	522.7	2	4C9	-1	0.52	0.23	0.75	11	-1		
79X01	522.7	524.3	1.6	4C9	-1	0.14	0.06	0.2	5	-1		
79X01	524.3	525.7	1.4	4K0	-1	0.1	0.04	0.14	3.5	-1		
79X01	525.7	526.7	1	4L0	-1	0.12	0.08	0.2	4	-1		
79X01	526.7	528.1	1.4	4L0	-1	0.11	0.04	0.15	6	-1		
79X01	528.1	528.8	0.7	4K0	-1	0.09	0.02	0.11	4	-1		
79X01	528.8	530.4	1.6	4A0	-1	0.02	0.02	0.04	0.1	-1		
79X01	530.4	532.3	1.9	WASTE	-1	-1	-1	-1	-1	-1		
79X01	532.3	532.9	0.6	4A0	-1	0.01	0.01	0.02	0.1	-1		
79X01	532.9	535	2.1	4K0	-1	0.11	0.05	0.16	6	-1		
79X01	535	536	1	4A0	-1	0.02	0.01	0.03	0.1	-1		
79X01	536	536.7	0.7	4K0	-1	0.12	0.06	0.18	8	-1		
79X01	536.7	538	1.3	4L0	-1	0.04	0.02	0.06	0.1	-1		
79X01	538	540.3	2.3	4K0	-1	0.07	0.04	0.11	3	-1		
79X01	540.3	545.4	5.1	WASTE	-1	-1	-1	-1	-1	-1		
79X01	545.4	546	0.6	4L0	-1	0.08	0.04	0.12	4	-1		
79X01	546	547.3	1.3	WASTE	-1	-1	-1	-1	-1	-1		
79X01	547.3	549.2	1.9	4C5	-1	0.13	0.06	0.19	2.5	-1		
79X01	549.2	550.1	0.9	4D9	-1	2.07	1.88	3.95	27	-1		
79X01	550.1	554.5	4.4	WASTE	-1	-1	-1	-1	-1	-1		
79X01	554.5	556.5	2	4A1	-1	2.2	3.19	5.39	39	-1	10.78	
79X01	556.5	558.5	2	4A1	-1	1.3	3.32	4.62	23	-1	9.24	
79X01	558.5	560.5	2	4A1	2.85	2.02	3.81	5.83	26	0.51	11.66	
79X01	560.5	561.6	1.1	4A1	2.74	2.16	5.27	7.43	33	0.38	8.173	5.61% /7.1m
79X01	561.6	650.9	89.3	WASTE	-1	-1	-1	-1	-1	-1	39.853	7.1
79X01	650.9	652.9	2	4A0	2.88	2.45	4.95	7.4	49	0.72	14.8	
79X01	652.9	654.9	2	4A0	2.76	1.93	4.45	6.38	29	0.62	12.76	
79X01	654.9	656.9	2	4A0	-1	1.65	3.65	5.3	27.5	-1	10.6	
79X01	656.9	658.9	2	4A0	-1	1.61	3.13	4.74	26	-1	9.48	
79X01	658.9	660.9	2	4A0	-1	1.4	2.07	3.47	25	-1	6.94	
79X01	660.9	662.7	1.8	4A0	-1	0.98	2.22	3.2	21	-1	5.76	5.11% /11.8m
79X01	662.7	681.3	18.6	WASTE	-1	-1	-1	-1	-1	-1	60.34	11.8
79X01	681.3	682.6	1.3	4C5	-1	2.01	3.65	5.66	27	-1	7.358	
79X01	682.6	683.5	0.9	4G0	-1	2.05	3.71	5.76	40	-1	5.184	5.70% /2.2m
79X01	683.5	772.2	88.7	WASTE	-1	-1	-1	-1	-1	-1	12.542	2.2



DY PROPERTY  
LENGTH WEIGHTED GRADE CALC'S

File: ASSYDAT.WR1

HOLE-ID	FROM (m)	TO (m)	INTERVAL	ROCK CODE	SG-PULP	Pb%	Zn%	Pb+Zn%	Ag(g/t)	Au(g/t)		
79X03	578.3	580.4	2.1	4L7	-1	0.42	0.14	0.56	6.5	-1		
79X03	580.4	581.5	1.1	4A3	-1	0.11	0.02	0.13	2	-1		
79X03	581.5	583.5	2	4C0	-1	0.66	0.22	0.88	8	-1		
79X03	583.5	585.5	2	4L0	-1	0.34	0.14	0.48	4	-1		
79X03	585.5	587.5	2	WASTE	-1	-1	-1	-1	-1	-1		
79X03	587.5	588.5	1	4L0	-1	0.26	0.03	0.29	3	-1		
79X03	588.5	590.1	1.6	5D9	-1	0.23	0.04	0.27	3	-1		
79X03	590.1	592.1	2	4L7	-1	0.04	0.02	0.06	2	-1		
79X03	592.1	594.1	2	4L7	-1	0.1	0.04	0.14	2	-1		
79X03	594.1	595.9	1.8	4L7	-1	0.13	0.11	0.24	1	-1		
79X03	595.9	597.1	1.2	4G49	-1	0.91	0.7	1.61	16	-1		
79X03	597.1	598.1	1	4L0	-1	0.13	0.07	0.2	2	-1		
79X03	598.1	599.3	1.2	4G49	-1	1.79	0.91	2.7	30	-1		
79X03	599.3	600.6	1.3	4G4	-1	3.34	1.92	5.26	45	-1		
79X03	600.6	602.3	1.7	4K649	-1	0.75	0.31	1.06	28	-1		
79X03	602.3	604.5	2.2	4E9	-1	0.38	0.13	0.51	27	-1		
79X03	604.5	606.7	2.2	4E9	-1	0.12	0.05	0.17	7	-1		
79X03	606.7	608.7	2	4L9	-1	0.11	0.04	0.15	13	-1		
79X03	608.7	610.2	1.5	4C9	-1	0.11	0.07	0.18	11	-1		
79X03	610.2	612	1.8	4C9	-1	0.65	0.58	1.23	16	-1		
79X03	612	614	2	4C9	-1	0.15	0.14	0.29	9	-1		
79X03	614	615.1	1.1	4C9	-1	0.04	0.03	0.07	5	-1		
79X03	615.1	616.6	1.5	4A9	-1	0.06	0.05	0.11	6	-1		
79X03	616.6	621.2	4.6	WASTE	-1	-1	-1	-1	-1	-1		
79X03	621.2	623.2	2	5A9	-1	0.02	0.02	0.04	0.5	-1		
79X03	623.2	624	0.8	4C9	-1	0.04	0.02	0.06	2	-1		
79X03	624	624.4	0.4	WASTE	-1	-1	-1	-1	-1	-1		
79X03	624.4	626.4	2	4L0	-1	0.01	0.03	0.04	0.1	-1		
79X03	626.4	628.4	2	4L0	-1	0.03	0.03	0.06	2	-1		
79X03	628.4	630.1	1.7	4L0	-1	0.02	0.03	0.05	1	-1		
79X03	630.1	631.9	1.8	5A9	-1	0.02	0.02	0.04	1	-1		
79X03	631.9	639	7.1	WASTE	-1	-1	-1	-1	-1	-1		
79X03	639	639.8	0.8	4C0	-1	0.1	0.05	0.15	8	-1		
79X03	639.8	641.8	2	4L0	-1	0.03	0.03	0.06	2	-1		
79X03	641.8	643.8	2	4L0	-1	0.03	0.02	0.05	2	-1		
79X03	643.8	644.4	0.6	4L0	-1	0.02	0.05	0.07	2	-1		
79X03	644.4	646.3	1.9	4C0	-1	0.13	0.05	0.18	7	-1		
79X03	646.3	700.8	54.5	WASTE	-1	-1	-1	-1	-1	-1		
79X03	700.8	702.8	2	4A4	-1	1.94	3.28	5.22	36	-1	10.44	
79X03	702.8	704.8	2	4A4	-1	1.48	2.72	4.2	29	-1	8.4	
79X03	704.8	706.4	1.6	4A4	-1	1.31	2.7	4.01	25	-1	6.416	4.51% /5.6m
79X03	706.4	713.6	7.2	WASTE	-1	-1	-1	-1	-1	-1	25.256	5.6
79X03	713.6	715.7	2.1	4A0	-1	0.27	0.31	0.58	5	-1		
79X03	715.7	717.2	1.5	WASTE	-1	-1	-1	-1	-1	-1		
79X03	717.2	719.3	2.1	4A0	-1	0.09	0.13	0.22	2	-1		
79X03	719.3	731.3	12	WASTE	-1	-1	-1	-1	-1	-1		
79X03	731.3	733.4	2.1	4L4	-1	1.88	0.94	2.82	25	-1		
79X03	733.4	735.4	2	4A0	-1	0.02	0.88	0.9	30	-1		
79X03	735.4	737.4	2	4A0	-1	0.01	0.26	0.27	16	-1		
79X03	737.4	739.4	2	4A0	-1	1.07	0.3	1.37	17	-1		
79X03	739.4	740.7	1.3	4A0	-1	0.08	0.16	0.24	7	-1		



BY PROPERTY  
LENGTH WEIGHTED GRADE CALC'S

File: ASSYDAT.WR1

HOLE-ID	FROM (m)	TO (m)	INTERVAL	ROCK CODE	SG-PULP	Pb%	Zn%	Pb+Zn%	Ag(g/t)	Au(g/t)
79X04	365.5	367	1.5	4L76	-1	0.05	0.03	0.08	2	-1
79X04	367	390.6	23.6	WASTE	-1	-1	-1	-1	-1	-1
79X04	390.6	391.9	1.3	4A0	-1	0.05	0.04	0.09	2	-1
79X04	391.9	392.3	0.4	WASTE	-1	-1	-1	-1	-1	-1
79X04	392.3	394.5	2.2	4A0	-1	0.05	0.03	0.08	3	-1
79X04	394.5	396.5	2	4K1	-1	0.03	0.01	0.04	6	-1
79X04	396.5	398.8	2.3	4C79	-1	0.04	0.01	0.05	-1	-1
79X04	398.8	400	1.2	4A0	-1	0.02	0.01	0.03	3	-1
79X04	400	400.5	0.5	4E0	-1	0.01	0.02	0.03	7	-1
79X04	400.5	582.2	181.7	WASTE	-1	-1	-1	-1	-1	-1
79X04	582.2	584.2	2	4D57	-1	2.21	5.19	7.4	50	-1
79X04	584.2	586.2	2	4A4	-1	0.68	1.03	1.71	12	-1
79X04	586.2	588.2	2	4A4	-1	3.62	3.41	7.03	46	-1
79X04	588.2	590	1.8	4A4	-1	2.64	3.34	5.98	40	-1
79X04	590	625.8	35.8	WASTE	-1	-1	-1	-1	-1	-1
79X04	625.8	626.8	1	4B0	4.05	4.79	11.95	16.74	90	0.55
79X04	626.8	627.8	1	4A41	3.03	2.72	5.93	8.65	47	0.34
79X04	627.8	629.1	1.3	4A41	3.05	3.6	7.13	10.73	66	0.55
79X04	629.1	630.6	1.5	4C0	3.33	3.66	6.87	10.53	56	0.93
79X04	630.6	632.6	2	4A1	-1	1.18	2.11	3.29	21	-1
79X04	632.6	634.5	1.9	4A1	-1	1.7	2.03	3.73	25	-1
79X04	634.5	689.1	54.6	WASTE	-1	-1	-1	-1	-1	-1
									68.801	8.7

$\frac{55.14}{4.8} = 11.5\%$

7.91% / 8.7m



DY PROPERTY  
LENGTH WEIGHTED GRADE CALC'S

File: ASSYDAT.WR1

HOLE-ID	FROM (m)	TO (m)	INTERVAL	ROCK CODE	SG-PULP	Pb%	Zn%	Pb+Zn%	Ag(g/t)	Au(g/t)		
79X06	671	672	1	4K7	-1	2.97	2.21	5.18	42	-1		
79X06	672	676.7	4.7	WASTE	-1	-1	-1	-1	-1	-1		
79X06	676.7	677.7	1	4K79	-1	4.24	3.44	7.68	61	-1		
79X06	677.7	678.1	0.4	WASTE	-1	-1	-1	-1	-1	-1		
79X06	678.1	679.4	1.3	4GB9	-1	4.71	4.39	9.1	88	-1		
79X06	679.4	706.6	27.2	WASTE	-1	-1	-1	-1	-1	-1		
79X06	706.6	708.5	1.9	4E89	4.51	4.08	2.92	7	57	2.92		
79X06	708.5	710.8	2.3	4G0	4.05	6.52	8.83	15.35	97	0.82		
79X06	710.8	713	2.2	WASTE	-1	-1	-1	-1	-1	-1		
79X06	713	714.3	1.3	4G18	4.29	7.32	5.5	12.82	82	0.93	16.666	
79X06	714.3	714.8	0.5	4L3	2.99	2.77	1.54	4.31	26	0.21	2.155	
79X06	714.8	716.1	1.3	4G18	4.58	4.62	3.73	8.35	58	1.23	10.855	
79X06	716.1	716.7	0.6	4D49	4.39	4.63	3.52	8.15	58	1.92	4.89	
79X06	716.7	717.4	0.7	4G148	-1	2.01	2.17	4.18	28	-1	2.926	
79X06	717.4	718.2	0.8	4D48	-1	2.77	1.69	4.46	46	-1	3.568	
79X06	718.2	720.2	2	4G148	4.61	7.47	6.96	14.43	100	0.86	28.86	
79X06	720.2	722.2	2	4G148	4.7	15.9	8.79	24.75	174	1.03	49.5	
79X06	722.2	724.2	2	4G148	4.47	15.3	9.31	24.65	181	0.86	49.3	
79X06	724.2	725.7	1.5	4G148	4.79	23.7	6.85	30.61	248	1.44	45.915	
79X06	725.7	726.7	1	4G148	4.88	21.1	4.59	25.72	237	2.13	25.72	
79X06	726.7	728.3	1.6	4E4	4.59	6.25	4.57	10.82	84	1.89	17.312	
79X06	728.3	730.5	2.2	4G0	4.48	6.48	8.05	14.53	99	0.89	31.966	
79X06	730.5	732.7	2.2	4G0	3.79	6.97	6.78	13.75	101	1.34	30.25	
79X06	732.7	734	1.3	4E9	-1	0.91	0.92	1.83	23	-1	2.379	
79X06	734	735.4	1.4	4E9	-1	4.25	2.35	6.6	60	-1	9.24	
79X06	735.4	737	1.6	4G48	4.81	4.62	5.7	10.32	140	1.72	16.512	
79X06	737	738	1	4G48	4.32	4.62	3.71	8.33	57	1.2	8.33	
79X06	738	738.5	0.5	5D69	2.87	0.09	0.17	0.26	6	0.69	0.13	
79X06	738.5	739.8	1.3	4G0	4.6	5.07	4.69	9.76	72	2.33	12.688	
79X06	739.8	741.8	2	4A0	-1	1.88	4.6	6.48	36	-1	12.96	
79X06	741.8	743.8	2	4A0	-1	1.81	3.45	5.26	33	-1	10.52	
79X06	743.8	745.5	1.7	4A0	-1	1.37	2.28	3.65	23	-1	6.205	
79X06	745.5	747.5	2	4A7	-1	0.92	1.37	2.29	22	-1	4.58	11.69% /34.5m
79X06	747.5	772.1	24.6	WASTE	-1	-1	-1	-1	-1	-1	403.427	34.5
79X06	772.1	774.1	2	4A4	-1	2.28	4.14	6.42	34	-1	12.84	
79X06	774.1	776.1	2	4A4	-1	2.61	4.79	7.4	46	-1	14.8	
79X06	776.1	777.3	1.2	4A4	-1	1.88	3.23	5.11	33	-1	6.132	6.49% /5.2m
79X06	777.3	782.1	4.8	WASTE	-1	-1	-1	-1	-1	-1	33.772	5.2
79X06	782.1	782.8	0.7	4G48	-1	9.55	7.41	16.96	114	-1	11.872	
79X06	782.8	783.3	0.5	4D489	-1	2.48	2.28	4.76	34	-1	2.38	11.88% /1.2m
79X06	783.3	783.9	0.6	4C9	-1	1.92	1.01	2.93	29	-1	14.252	1.2
79X06	783.9	785.2	1.3	4A79	-1	0.18	0.21	0.39	8	-1		
79X06	785.2	786.4	1.2	4L37	-1	0.12	0.11	0.23	5	-1		
79X06	786.4	788	1.6	4A0	-1	0.58	0.86	1.44	10	-1		
79X06	788	788.9	0.9	4C0	-1	0.37	0.2	0.57	14	-1		
79X06	788.9	789.5	0.6	4G0	-1	2.41	2.41	4.82	38	-1		
79X06	789.5	790.1	0.6	4E89	-1	1.17	0.52	1.69	30	-1		

BY PROPERTY  
 LENGTH WEIGHTED GRADE CALC'S

File: ASSYDAT.WR1

79X06	790.1	790.5	0.4	4G8	-1	3.61	7.3	10.91	63	-1
79X06	790.5	791	0.5	4G9	-1	0.71	0.41	1.12	19	-1
79X06	791	791.7	0.7	4L7	-1	0.48	0.35	0.83	8	-1
79X06	791.7	793.6	1.9	WASTE	-1	-1	-1	-1	-1	-1
79X06	793.6	794.5	0.9	4G9	-1	2.47	2.23	4.7	39	-1
79X06	794.5	796.6	2.1	4E89	-1	0.28	0.18	0.46	20	-1
79X06	796.6	797.8	1.2	4G89	-1	1.99	2.45	4.44	33	-1
79X06	797.8	799.5	1.7	4A0	-1	0.24	0.15	0.39	8	-1
79X06	799.5	800.6	1.1	4L37	-1	0.14	0.07	0.21	2	-1
79X06	800.6	801.6	1	4A0	-1	0.31	0.1	0.41	7	-1
79X06	801.6	802.9	1.3	WASTE	-1	-1	-1	-1	-1	-1
79X06	802.9	804.2	1.3	4G89	-1	0.64	0.38	1.02	19	-1
79X06	804.2	805.7	1.5	4G89	-1	1.23	0.61	1.84	27	-1
79X06	805.7	812.6	6.9	WASTE	-1	-1	-1	-1	-1	-1
79X06	812.6	814.3	1.7	4L67	-1	0.03	0.03	0.06	6	-1
79X06	814.3	816.1	1.8	4L17	-1	0.02	0.03	0.05	2	-1
79X06	816.1	817.9	1.8	4L67	-1	0.01	0.03	0.04	2	-1
79X06	817.9	872.5	54.6	WASTE	-1	-1	-1	-1	-1	-1
79X06	872.5	873.2	0.7	4L7	-1	0.19	0.42	0.61	19	-1
79X06	873.2	874.2	1	4A0	-1	0.07	0.02	0.09	2	-1
79X06	874.2	875.7	1.5	4A0	-1	0.07	0.06	0.13	1	-1
79X06	875.7	878	2.3	4A4	-1	1.97	3.57	5.54	29	-1
79X06	878	878.8	0.8	4G0	-1	3.17	5.01	8.18	56	-1
79X06	878.8	879.2	0.4	4A0	-1	0.66	0.47	1.13	15	-1
79X06	879.2	956.7	77.5	WASTE	-1	-1	-1	-1	-1	-1

BY PROPERTY  
LENGTH WEIGHTED GRADE CALC'S

File: ASSYDAT.WR1

HOLE-ID	FROM (m)	TO (m)	INTERVAL	ROCK CODE	SG-PULP	Pb%	Zn%	Pb+Zn%	Ag(g/t)	Au(g/t)		
79X07	544	545.8	1.8	4A0	-1	1.51	3.28	4.79	28	-1		
79X07	545.8	568.4	22.6	WASTE	-1	-1	-1	-1	-1	-1		
79X07	568.4	570.2	1.8	4A0	-1	0.26	0.49	0.75	4	-1		
79X07	570.2	572.2	2	4A0	-1	0.02	0.03	0.05	1	-1		
79X07	572.2	574.2	2	4A0	-1	0.32	0.45	0.77	4	-1		
79X07	574.2	576.1	1.9	4G0	4.16	1.87	4.55	6.42	32	0.34	12.198	
79X07	576.1	577.8	1.7	4G0	4.25	2.13	5.88	8.01	34	0.48	13.617	
79X07	577.8	578.6	0.8	4G0	4.47	6.78	16.2	22.98	150	1.2	18.384	
79X07	578.6	580.3	1.7	4D4	3.36	2.17	4.7	6.87	35	0.51	11.679	
79X07	580.3	581.4	1.1	4D4	3.05	3.61	7.76	11.37	83	0.34	12.507	
79X07	581.4	583.3	1.9	4D4	4.32	6.76	9.52	16.28	104	1.44	30.932	
79X07	583.3	585.2	1.9	4D4	3.07	4.41	9.85	14.26	3	0.1	27.094	
79X07	585.2	586.8	1.6	4A14	3.97	5.51	10.2	15.71	80	0.65	25.136	
												12.03% /12.6m
79X07	586.8	588.8	2	5A0	-1	0.37	0.77	1.14	5	-1	151.547	12.6
79X07	588.8	792.7	203.9	WASTE	-1	-1	-1	-1	-1	-1		

*Rec # 30*

DY PROPERTY  
LENGTH WEIGHTED GRADE CALC'S

File: ASSYDAT.WR1

HOLE-ID	FROM (m)	TO (m)	INTERVAL	ROCK CODE	SG-PULP	Pb%	Zn%	Pb+Zn%	Ag(g/t)	Au(g/t)		
79X08	502.5	503.6	1.1	4L75	-1	0.53	0.2	0.73	12	-1		
79X08	503.6	505.5	1.9	4L75	-1	0.19	0.17	0.36	5	-1		
79X08	505.5	507	1.5	4L37	-1	0.24	0.1	0.34	5	-1		
79X08	507	508.2	1.2	4L37	-1	0.14	0.27	0.41	5	-1		
79X08	508.2	509.5	1.3	4D0	-1	2.98	2.57	5.55	38	-1	7.215	
79X08	509.5	510.6	1.1	4G8	-1	3.71	2.95	6.66	46	-1	7.326	6.06% /2.4m
79X08	510.6	511.5	0.9	4L374	-1	0.45	0.16	0.61	8	-1	14.541	2.4
79X08	511.5	513.1	1.6	4C89	-1	1.49	1.14	2.63	21	-1		
79X08	513.1	515.2	2.1	4C09	-1	0.36	0.36	0.72	24	-1		
79X08	515.2	516.6	1.4	4C79	-1	0.05	0.08	0.13	11	-1		
79X08	516.6	517.9	1.3	4C79	-1	0.05	0.09	0.14	12	-1		
79X08	517.9	518.2	0.3	5D6	-1	0.17	0.07	0.24	13	-1		
79X08	518.2	518.9	0.7	4C789	-1	0.05	0.09	0.14	8	-1		
79X08	518.9	519.9	1	5D6	-1	0.02	0.04	0.06	4	-1		
79X08	519.9	521.4	1.5	4D89	-1	0.92	0.67	1.59	22	-1		
79X08	521.4	522.5	1.1	4D89	-1	0.77	0.61	1.38	20	-1		
79X08	522.5	524.5	2	4C89	-1	0.54	1.31	1.85	18	-1		
79X08	524.5	526.5	2	4C89	-1	0.81	2.78	3.59	18	-1		
79X08	526.5	528.5	2	4C89	-1	0.44	0.32	0.76	15	-1		
79X08	528.5	529.3	0.8	4L0	-1	0.03	0.04	0.07	6	-1		
79X08	529.3	531.3	2	4C89	-1	0.26	0.2	0.46	13	-1		
79X08	531.3	533.3	2	4C89	-1	0.26	0.38	0.64	15	-1		
79X08	533.3	535.3	2	4C8	-1	0.04	0.05	0.09	3	-1		
79X08	535.3	536.8	1.5	4C89	-1	0.1	0.06	0.16	15	-1		
79X08	536.8	537.4	0.6	4E9	-1	0.1	0.09	0.19	14	-1		
79X08	537.4	538.6	1.2	4C89	-1	0.15	0.07	0.22	15	-1		
79X08	538.6	539.9	1.3	4C9	-1	1.21	0.91	2.12	24	-1		
79X08	539.9	541.5	1.6	4C9	-1	0.83	0.44	1.27	19	-1		
79X08	541.5	543.5	2	4C9	-1	0.89	0.6	1.49	21	-1		
79X08	543.5	544.4	0.9	4K19	-1	0.98	0.6	1.58	21	-1		
79X08	544.4	545.6	1.2	4C79	-1	0.65	0.25	0.9	32	-1		
79X08	545.6	547.2	1.6	4K9	-1	0.43	0.6	1.03	12	-1		
79X08	547.2	549.2	2	4G9	-1	3.73	4.88	8.61	66	-1		
79X08	549.2	550.4	1.2	4G9	-1	1.84	1.43	3.27	35	-1		
79X08	550.4	551.3	0.9	4C89	-1	0.32	0.37	0.69	12	-1		
79X08	551.3	552	0.7	4D8	-1	1.93	2	3.93	28	-1		
79X08	552	554	2	4L728	-1	0.25	0.3	0.55	8	-1		
79X08	554	555.5	1.5	4L7	-1	0.53	0.28	0.81	10	-1		
79X08	555.5	558	2.5	WASTE	-1	-1	-1	-1	-1	-1		
79X08	558	560	2	4L7	-1	0.01	0.03	0.04	2	-1		
79X08	560	562	2	4L7	-1	0.09	0.08	0.17	4	-1		
79X08	562	564	2	4L7	-1	0.02	0.04	0.06	2	-1		
79X08	564	566	2	4L7	-1	0.07	0.06	0.13	3	-1		
79X08	566	566.7	0.7	4L7	-1	0.09	0.1	0.19	3	-1		
79X08	566.7	567.1	0.4	4H9	-1	0.92	1.03	1.95	18	-1		
79X08	567.1	568.1	1	4L719	-1	0.59	0.46	1.05	14	-1		
79X08	568.1	569	0.9	4D89	-1	1.9	1.37	3.27	27	-1		
79X08	569	569.5	0.5	4L1	-1	0.63	0.67	1.3	11	-1		
79X08	569.5	572	2.5	4G489	4.3	3.96	4.28	8.24	59	1.99	20.6	
79X08	572	573.2	1.2	4A4	2.96	1.88	3.6	5.48	29	2.33	6.576	7.34% /3.7m

DY PROPERTY  
LENGTH WEIGHTED GRADE CALC'S

File: ASSYDAT.WR1

79X08	573.2	574.2	1	4K19	-1	0.2	0.11	0.31	19	-1	27.176	3.7
79X08	574.2	576.2	2	4A9	-1	0.77	0.42	1.19	19	-1		
79X08	576.2	577.7	1.5	4C79	-1	0.55	0.2	0.75	20	-1		
79X08	577.7	579.7	2	5A7	-1	0.07	0.09	0.16	5	-1		
79X08	579.7	581.9	2.2	4L7	-1	0.01	0.02	0.03	3	-1		
79X08	581.9	586.6	4.7	WASTE	-1	-1	-1	-1	-1	-1		
79X08	586.6	588.3	1.7	4A0	-1	0.3	0.53	0.83	6	-1		
79X08	588.3	588.7	0.4	4L27	-1	0.06	0.29	0.35	3	-1		
79X08	588.7	589.1	0.4	4A0	-1	0.06	0.39	0.45	4	-1		
79X08	589.1	592.4	3.3	4C7	-1	0.08	0.28	0.36	4	-1		
79X08	592.4	592.9	0.5	4A0	-1	0.1	0.06	0.16	4	-1		
79X08	592.9	593.8	0.9	4L679	-1	0.34	0.45	0.79	20	-1		
79X08	593.8	595.8	2	4L7	-1	0.01	0.01	0.02	1	-1		
79X08	595.8	597.2	1.4	4L6	-1	0.24	0.02	0.26	4	-1		
79X08	597.2	597.5	0.3	4C9	-1	1.79	1.37	3.16	30	-1		
79X08	597.5	598	0.5	4K0	-1	0.42	0.74	1.16	16	-1		
79X08	598	599.2	1.2	4K0	-1	0.82	0.39	1.21	16	-1		
79X08	599.2	600.2	1	4E9	-1	0.51	0.21	0.72	14	-1		
79X08	600.2	602.3	2.1	4L0	-1	0.19	0.21	0.4	4	-1		
79X08	602.3	605.3	3	4L9	-1	0.13	0.11	0.24	5	-1		
79X08	605.3	606.2	0.9	4C79	-1	0.3	0.03	0.33	8	-1		
79X08	606.2	608	1.8	4L79	-1	0.13	0.03	0.16	5	-1		
79X08	608	610.2	2.2	4C7	-1	0.38	0.76	1.14	11	-1		
79X08	610.2	610.8	0.6	4A0	-1	0.04	0.02	0.06	5	-1		
79X08	610.8	616.2	5.4	WASTE	-1	-1	-1	-1	-1	-1		
79X08	616.2	617.8	1.6	4C78	-1	0.14	1.02	1.16	6	-1		
79X08	617.8	618.8	1	4C78	-1	0.17	0.33	0.5	5	-1		
79X08	618.8	620.5	1.7	4L65	-1	0.05	0.43	0.48	3	-1		
79X08	620.5	622	1.5	4E879	-1	2.5	1.37	3.87	40	-1		
79X08	622	623.3	1.3	4E879	-1	1.87	1.11	2.98	24	-1		
79X08	623.3	624.6	1.3	4G8	-1	4.2	3.6	7.8	53	-1		
79X08	624.6	675.2	50.6	WASTE	-1	-1	-1	-1	-1	-1		
79X08	675.2	676.3	1.1	4A4	-1	1.56	2.99	4.55	25	-1	5.005	
79X08	676.3	677.7	1.4	4G0	1.9	4.61	5.76	10.37	97	0.38	14.518	
79X08	677.7	679.1	1.4	4G0	4.04	4.94	6.34	11.28	113	1.92	15.792	
79X08	679.1	680.5	1.4	4A4	2.95	2.64	4.02	6.66	43	0.86	9.324	
79X08	680.5	681.5	1	4A4	2.62	2.3	3.84	6.14	36	0.89	6.14	
79X08	681.5	683.5	2	4A0	-1	1.57	2.4	3.97	25	-1	7.94	7.07% /8.3m
79X08	683.5	685.5	2	4A0	-1	0.69	0.91	1.6	13	-1	58.719	8.3
79X08	685.5	687.5	2	4A0	-1	0.74	1.35	2.09	13	-1		
79X08	687.5	689.1	1.6	4A0	-1	0.65	0.96	1.61	13	-1		
79X08	689.1	689.4	0.3	5D6	-1	0.03	0.03	0.06	3	-1		
79X08	689.4	691	1.6	4A0	-1	0.81	0.92	1.73	16	-1		
79X08	691	692.9	1.9	4A0	-1	0.92	1.41	2.33	18	-1		
79X08	692.9	695.1	2.2	4L1	-1	1.21	1.38	2.59	17	-1		
79X08	695.1	696.6	1.5	4A0	-1	0.9	2.08	2.98	14	-1		
79X08	696.6	750	53.4	WASTE	-1	-1	-1	-1	-1	-1		
79X08	750	751.4	1.4	4A4	-1	0.85	2.02	2.87	9	-1		
79X08	751.4	752.4	1	4A4	-1	2.84	2.79	5.63	25	-1		
79X08	752.4	754.4	2	4A7	-1	0.17	0.1	0.27	3	-1		
79X08	754.4	755.7	1.3	4A7	-1	0.09	0.07	0.16	3	-1		
79X08	755.7	756.7	1	5D0	-1	0.14	0.24	0.38	3	-1		
79X08	756.7	757.3	0.6	4A9	-1	0.91	1.46	2.37	14	-1		

DY PROPERTY  
LENGTH WEIGHTED GRADE CALC'S

File: ASSYDAT.WR1

79X08	757.3	759.4	2.1	4C9	-1	2.51	3.45	5.96	36	-1
79X08	759.4	761	1.6	WASTE	-1	-1	-1	-1	-1	-1
79X08	761	761.8	0.8	4L7	-1	0.08	0.11	0.19	4	-1
79X08	761.8	956.7	194.9	WASTE	-1	-1	-1	-1	-1	-1

DY PROPERTY  
LENGTH WEIGHTED GRADE CALC'S

File: ASSYDAT.WR1

HOLE-ID	FROM (m)	TO (m)	INTERVAL	ROCK CODE	SG-PULP	Pb%	Zn%	Pb+Zn%	Ag(g/t)	Au(g/t)		
79X09	502.6	504.6	2	4L3	-1	0.01	0.01	0.02	3	-1		
79X09	504.6	506.8	2.2	4L3	-1	0.02	0.01	0.03	3	-1		
79X09	506.8	509.1	2.3	4K9	-1	0.05	0.01	0.06	12	-1		
79X09	509.1	510.4	1.3	4K9	-1	0.03	0.01	0.04	7	-1		
79X09	510.4	510.9	0.5	4K89	-1	0.09	0.03	0.12	13	-1		
79X09	510.9	511.6	0.7	4K9	-1	0.32	0.25	0.57	14	-1		
79X09	511.6	513.6	2	4K9	-1	0.43	0.29	0.72	14	-1		
79X09	513.6	514.6	1	4K0	-1	0.05	0.01	0.06	7	-1		
79X09	514.6	515.6	1	4C0	-1	0.04	0.01	0.05	7	-1		
79X09	515.6	517.6	2	4A0	-1	0.03	0.01	0.04	4	-1		
79X09	517.6	519.6	2	4A0	-1	0.03	0.02	0.05	3	-1		
79X09	519.6	521.6	2	4A0	-1	0.02	0.02	0.04	4	-1		
79X09	521.6	522.2	0.6	4A0	-1	0.02	0.01	0.03	4	-1		
79X09	522.2	523.6	1.4	4C0	-1	0.09	0.05	0.14	6	-1		
79X09	523.6	525	1.4	4A0	-1	0.03	0.01	0.04	5	-1		
79X09	525	525.6	0.6	4C0	-1	0.03	0.02	0.05	4	-1		
79X09	525.6	526.4	0.8	4K0	-1	0.07	0.09	0.16	11	-1		
79X09	526.4	527.6	1.2	4C0	-1	0.13	0.09	0.22	7	-1		
79X09	527.6	528.8	1.2	4K0	-1	0.13	0.05	0.18	14	-1		
79X09	528.8	530	1.2	4A1	-1	0.83	1.26	2.09	17	-1		
79X09	530	531.2	1.2	4A1	-1	1.17	1.36	2.53	23	-1		
79X09	531.2	532.5	1.3	4C0	-1	0.08	0.06	0.14	4	-1		
79X09	532.5	534.1	1.6	4A0	-1	1.4	1.78	3.18	28	-1		
79X09	534.1	535.9	1.8	4L627	-1	0.68	0.68	1.36	14	-1		
79X09	535.9	536.2	0.3	4A4	-1	1.51	4.92	6.43	19	-1		
79X09	536.2	580.2	44	WASTE	-1	-1	-1	-1	-1	-1		
79X09	580.2	582.2	2	4A4	-1	1.63	4.75	6.38	32	-1	12.76	
79X09	582.2	584.2	2	4A4	-1	1.82	3.64	5.46	30	-1	10.92	
79X09	584.2	586.2	2	4A4	-1	1.89	4.77	6.66	33	-1	13.32	
79X09	586.2	587.6	1.4	4A4	-1	1.24	2.76	4	26	-1	5.6	5.76% /7.4m
79X09	587.6	592.8	5.2	WASTE	-1	-1	-1	-1	-1	-1	42.6	7.4
79X09	592.8	595	2.2	4A0	-1	1.02	0.79	1.81	11	-1		
79X09	595	597.2	2.2	4L6	-1	0.89	2.01	2.9	11	-1		
79X09	597.2	597.9	0.7	4A0	-1	0.49	2.65	3.14	9	-1		
79X09	597.9	598.1	0.2	5D3	-1	0.05	0.1	0.15	2	-1		
79X09	598.1	600.3	2.2	4A0	-1	1	2.83	3.83	17	-1	8.426	
79X09	600.3	602.5	2.2	4A0	-1	0.82	2.68	3.5	15	-1	7.7	
79X09	602.5	604.5	2	4L7	-1	1.56	4.09	5.65	23	-1	11.3	
79X09	604.5	606	1.5	4L7	-1	2.31	5.15	7.46	34	-1	11.19	
79X09	606	607.7	1.7	4L4	-1	1	2.65	3.65	16	-1	6.205	4.67% /9.6m
79X09	607.7	609.1	1.4	4A0	-1	0.23	0.35	0.58	5	-1	44.821	9.6
79X09	609.1	609.9	0.8	5D3	-1	0.09	0.23	0.32	3	-1		
79X09	609.9	611.3	1.4	4L47	-1	0.4	1.53	1.93	7	-1		
79X09	611.3	612.6	1.3	4D1	-1	1.6	4.54	6.14	26	-1	7.982	
79X09	612.6	614.6	2	4L14	-1	3.53	3.94	7.47	52	-1	14.94	
79X09	614.6	616.6	2	4L14	-1	1.54	1.37	2.91	24	-1	5.82	
79X09	616.6	618.3	1.7	4L14	-1	1.77	1.59	3.36	23	-1	5.712	
79X09	618.3	620.3	2	4D14	-1	1.46	1.55	3.01	22	-1	6.02	

BY PROPERTY  
LENGTH WEIGHTED GRADE CALC'S

File: ASSYDAT.WR1

79X09	620.3	622	1.7	4D14	-1	1.33	2.05	3.38	18	-1	5.746	
79X09	622	622.7	0.7	4D14	-1	2.15	6.04	8.19	38	-1	5.733	
79X09	622.7	623.1	0.4	5D3	-1	1.35	3.32	4.67	23	-1	1.868	
79X09	623.1	624.1	1	4L14	-1	2.32	6.32	8.64	48	-1	8.64	4.88% /12.8m
79X09	624.1	625.6	1.5	5D3	-1	0.39	1.07	1.46	7	-1	62.461	12.8
79X09	625.6	627.2	1.6	4L6	-1	0.27	0.83	1.1	6	-1		
79X09	627.2	627.8	0.6	4L4	-1	0.16	0.69	0.85	3	-1		
79X09	627.8	629.7	1.9	5D3	-1	0.19	0.38	0.57	8	-1		
79X09	629.7	630.2	0.5	4L147	-1	0.69	1.81	2.5	14	-1		
79X09	630.2	632	1.8	4A7	-1	0.34	1.28	1.62	6	-1		
79X09	632	634	2	4A0	-1	0.56	1.13	1.69	11	-1		
79X09	634	636	2	4A0	-1	0.23	0.27	0.5	5	-1		
79X09	636	636.8	0.8	4A0	-1	1.55	1.58	3.13	28	-1	2.504	
79X09	636.8	638.8	2	4A4	2.77	3.78	5.51	9.29	51	0.65	18.58	
79X09	638.8	640.1	1.3	4A4	2.91	3.55	5.72	9.27	47	0.69	12.051	
79X09	640.1	640.9	0.8	4D9	3.61	4.52	4.76	9.28	46	2.3	7.424	
79X09	640.9	642.9	2	4D1	3.22	3.55	4.03	7.58	50	0.86	15.16	
79X09	642.9	644.9	2	4D1	3.11	1.47	2.76	4.23	26	1.82	8.46	
79X09	644.9	646.9	2	4D1	3.24	3.33	5.62	8.95	50	1.23	17.9	
79X09	646.9	648.4	1.5	4D1	-1	1.29	2.23	3.52	26	-1	5.28	
79X09	648.4	649.2	0.8	4C0	-1	0.59	0.81	1.4	13	-1	1.12	
79X09	649.2	651	1.8	4D0	-1	2.36	2.28	4.64	35	-1	8.352	
79X09	651	653	2	4C9	-1	0.65	0.87	1.52	19	-1	3.04	
79X09	653	653.5	0.5	4D0	-1	2.55	4.23	6.78	40	-1	3.39	
79X09	653.5	654.3	0.8	4L4	-1	0.37	0.82	1.19	6	-1	0.952	
79X09	654.3	656.1	1.8	4A0	-1	3.06	4.39	7.45	49	-1	13.41	5.85% /20.1m
79X09	656.1	657.3	1.2	WASTE	-1	-1	-1	-1	-1	-1	117.623	20.1
79X09	657.3	658.3	1	4A4	-1	2.16	6.89	9.05	35	-1		
79X09	658.3	795.3	137	WASTE	-1	-1	-1	-1	-1	-1		

Handwritten calculation:  

$$\frac{79.55}{10.1} = 7.88\%$$
 with a note "10.1m" and an arrow pointing to the denominator.

BY PROPERTY  
LENGTH WEIGHTED GRADE CALC'S

File: ASSYDAT.WR1

HOLE-ID	FROM (m)	TO (m)	INTERVAL	ROCK CODE	SG-PULP	Pb%	Zn%	Pb+Zn%	Ag(g/t)	Au(g/t)		
79X11	742.1	742.6	0.5	WASTE	-1	6.3	8.3	14.6	109	-1		
79X11	742.6	743.3	0.7	4G49	-1	1.01	0.67	1.68	16	-1		
79X11	743.3	745.6	2.3	4C9	-1	-1	-1	-1	-1	-1		
79X11	745.6	747.7	2.1	WASTE	-1	1.41	0.95	2.36	15	-1		
79X11	747.7	749.7	2	4K9	4.46	6.5	0.93	7.43	36	1.82	14.86	
79X11	749.7	750.9	1.2	4K89	4.33	7.78	6.44	14.22	103	1.03	17.064	
79X11	750.9	751.5	0.6	4G48	4.5	3.73	2.97	6.7	50	1.78	4.02	
79X11	751.5	753	1.5	4K8	4.63	7.07	5.8	12.87	92	1.03	19.305	
79X11	753	754	1	4G48	4.6	6.86	3.12	9.98	73	1.82	9.98	
79X11	754	755.4	1.4	4K8	4.57	6.12	6.66	12.78	89	0.82	17.892	10.79% /7.7m
79X11	755.4	757.2	1.8	4G483	-1	1.37	0.99	2.36	25	-1	83.121	7.7
79X11	757.2	762.7	5.5	4K89	-1	-1	-1	-1	-1	-1		
79X11	762.7	763.5	0.8	WASTE	4.12	7	5.84	12.84	80	0.55	10.272	
79X11	763.5	765.5	2	4D87	4.33	5.4	5.8	11.2	86	0.48	22.4	
79X11	765.5	767.1	1.6	4G483	4.38	5.61	9.18	14.79	74	0.45	23.664	
79X11	767.1	769.6	2.5	4A4	2.66	1.91	3.6	5.51	27	0.48	13.775	
79X11	769.6	770.1	0.5	4A4	4.37	5.17	6.94	12.11	90	1.06	6.055	10.29% /7.4m
79X11	770.1	779.2	9.1	4E1	-1	-1	-1	-1	-1	-1	76.166	7.4
79X11	779.2	779.8	0.6	WASTE	-1	1.78	2.76	4.54	36	-1	2.724	
79X11	779.8	781.5	1.7	4E9	4.5	11.8	7.87	19.73	143	1.41	33.541	
79X11	781.5	783	1.5	4G43	4.5	7.24	5	12.24	99	1.27	18.36	
79X11	783	784.7	1.7	4G43	4.5	8.05	9.44	17.49	145	1.92	29.733	
79X11	784.7	785.7	1	4G43	4.61	2.56	0.81	3.37	47	1.27	3.37	
79X11	785.7	787.2	1.5	4K469	4.66	7.36	8.45	15.81	92	1.03	23.715	
79X11	787.2	789.2	2	4K46	4.1	3.32	2.63	5.95	67	0.79	11.9	
79X11	789.2	790.7	1.5	4K469	4.61	7.26	8.79	16.05	92	0.51	24.075	
79X11	790.7	792.3	1.6	4G43	4.45	4.8	3.36	8.16	77	0.48	13.056	
79X11	792.3	793.6	1.3	4E84	4.24	1.2	1.11	2.31	39	0.58	3.003	
79X11	793.6	795	1.4	4E849	4.39	6.02	6.27	12.29	89	0.93	17.206	
79X11	795	796.2	1.2	4G483	4.74	5.44	5.21	10.65	71	0.79	12.78	
79X11	796.2	797.7	1.5	4G483	-1	3.23	2.16	5.39	35	-1	8.085	
79X11	797.7	799.7	2	4D84	-1	2.53	3.36	5.89	34	-1	11.78	
79X11	799.7	801.7	2	4D789	-1	1.77	3.48	5.25	28	-1	10.5	
79X11	801.7	802.9	1.2	4D789	-1	2.35	5.46	7.81	34	-1	9.372	9.84% /23.7m
79X11	802.9	804.3	1.4	4D784	-1	0.63	0.77	1.4	13	-1	233.2	23.7
79X11	804.3	805.2	0.9	4D789	-1	1.43	0.7	2.13	21	-1		
79X11	805.2	807.4	2.2	4A739	-1	-1	-1	-1	-1	-1		
79X11	807.4	808.9	1.5	4A739	-1	0.15	0.1	0.25	6	-1		
79X11	808.9	810.5	1.6	4L179	-1	0.2	0.36	0.56	9	-1		
79X11	810.5	812.2	1.7	4L179	-1	0.39	1.22	1.61	12	-1		
79X11	812.2	813.8	1.6	4L179	-1	0.15	0.19	0.34	9	-1		
79X11	813.8	819.1	5.3	4L179	-1	-1	-1	-1	-1	-1		
79X11	819.1	819.8	0.7	WASTE	-1	1.77	2.18	3.95	27	-1		
79X11	819.8	829.3	9.5	4E0	-1	-1	-1	-1	-1	-1		
79X11	829.3	830.9	1.6	WASTE	-1	0.06	0.06	0.12	4	-1		
79X11	830.9	832	1.1	4A0	-1	0.02	0.1	0.12	2	-1		
79X11	832	834.5	2.5	5D9	-1	0.32	0.21	0.53	6	-1		







BY PROPERTY  
LENGTH WEIGHTED GRADE CALC'S

File: ASSYDAT.WR1

HOLE-ID	FROM (m)	TO (m)	INTERVAL	ROCK CODE	SG-PULP	Pb%	Zn%	Pb+Zn%	Ag(g/t)	Au(g/t)		
79X14	686.3	688.6	2.3	4C89	-1	3.7	2.76	6.46	49	-1		
79X14	688.6	689	0.4	4L9	-1	0.18	0.14	0.32	8	-1		
79X14	689	689.8	0.8	4C289	-1	1.52	0.77	2.29	22	-1		
79X14	689.8	690.6	0.8	4L0	-1	0.02	0.01	0.03	0.1	-1		
79X14	690.6	704.1	13.5	WASTE	-1	-1	-1	-1	-1	-1		
79X14	704.1	705.7	1.6	4C79	-1	1.68	0.87	2.55	20	-1		
79X14	705.7	706.4	0.7	4A0	-1	0.47	0.35	0.82	2	-1		
79X14	706.4	708.4	2	4G89	-1	3.81	2.98	6.79	51	-1	13.58	
79X14	708.4	710.4	2	4G8	-1	3.26	2.92	6.18	47	-1	12.36	
79X14	710.4	712.5	2.1	4G8	-1	3.43	2.91	6.34	42	-1	13.314	6.44% /6.1m
79X14	712.5	713	0.5	4L79	-1	0.79	0.67	1.46	15	-1	39.254	6.1
79X14	713	714.3	1.3	4A0	-1	0.19	0.11	0.3	3	-1		
79X14	714.3	715.5	1.2	4L2	-1	1.24	1.18	2.42	23	-1		
79X14	715.5	717.5	2	4G89	-1	3.54	2.84	6.38	42	-1	12.76	
79X14	717.5	719.5	2	4G89	4.52	3.86	3.35	7.21	53	0.93	14.42	
79X14	719.5	720.5	1	4G8	4.44	5.53	6.08	11.61	78	0.93	11.61	
79X14	720.5	720.8	0.3	4E0	-1	2.2	1.97	4.17	58	-1	1.251	
79X14	720.8	722.2	1.4	4A0	-1	1.43	2.13	3.56	25	-1	4.984	
79X14	722.2	723.9	1.7	4A0	-1	1.5	2.96	4.46	23	-1	7.582	6.26% /8.4m
79X14	723.9	734.1	10.2	WASTE	-1	-1	-1	-1	-1	-1	52.607	8.4
79X14	734.1	734.9	0.8	4C2	-1	0.19	0.53	0.72	6	-1		
79X14	734.9	742	7.1	WASTE	-1	-1	-1	-1	-1	-1		
79X14	742	743.9	1.9	4L42	-1	0.73	0.2	0.93	5	-1		
79X14	743.9	745.9	2	4L629	-1	0.51	2.07	2.58	8	-1		
79X14	745.9	747.9	2	4L629	-1	0.07	0.08	0.15	3	-1		
79X14	747.9	749.9	2	4L629	-1	0.1	0.2	0.3	15	-1		
79X14	749.9	787.7	37.8	WASTE	-1	-1	-1	-1	-1	-1		
79X14	787.7	788.3	0.6	4C9	-1	1.95	2.92	4.87	34	-1		
79X14	788.3	788.8	0.5	4E9	-1	0.8	1.01	1.81	22	-1		
79X14	788.8	789.1	0.3	4G4	-1	7.1	7.87	14.97	85	-1	4.491	
79X14	789.1	790.3	1.2	4E9	-1	0.59	0.71	1.3	22	-1	1.56	
79X14	790.3	791.6	1.3	4D46	3.61	3.07	5.4	8.47	59	0.99	11.011	
79X14	791.6	792.1	0.5	4G0	4.33	5.68	7.93	13.61	70	0.96	6.805	
79X14	792.1	792.7	0.6	4D6	4.31	4.17	4.9	9.07	56	0.79	5.442	
79X14	792.7	794.2	1.5	4E4	4.78	5.26	4.9	10.16	66	1.75	15.24	
79X14	794.2	794.5	0.3	4G9	4.77	2.95	4.87	7.82	50	2.4	2.346	
79X14	794.5	795.7	1.2	4E49	4.3	4.95	1.58	6.53	62	1.75	7.836	
79X14	795.7	796.1	0.4	4H2	4.42	8.37	5.84	14.21	115	1.03	5.684	
79X14	796.1	798.1	2	4K41	4.35	6.94	6.08	13.02	80	1.61	26.04	
79X14	798.1	800.1	2	4K491	4.59	7.2	3.7	10.9	88	1.65	21.8	
79X14	800.1	802.1	2	4K491	4.36	2.14	2.1	4.24	31	2.61	8.48	
79X14	802.1	804.1	2	4K491	4.53	3.51	1.69	5.2	36	2.02	10.4	
79X14	804.1	804.6	0.5	4K41	4.37	7.82	9.18	17	93	1.51	8.5	
79X14	804.6	805.1	0.5	4G4	4.62	5.04	6.33	11.37	56	1.2	5.685	
79X14	805.1	807.1	2	4K491	-1	2.78	2.74	5.52	43	-1	11.04	
79X14	807.1	808.7	1.6	4K491	-1	0.55	0.52	1.07	19	-1	1.712	
79X14	808.7	809.1	0.4	4G4	-1	7.62	9.96	17.58	87	-1	7.032	
79X14	809.1	811.5	2.4	5D3	-1	0.07	0.06	0.13	5	-1	0.312	





BY PROPERTY  
LENGTH WEIGHTED GRADE CALC'S

File: ASSYDAT.WR1

HOLE-ID	FROM (m)	TO (m)	INTERVAL	ROCK CODE	SG-PULP	Pb%	Zn%	Pb+Zn%	Ag(g/t)	Au(g/t)	
79X16	641.5	642	0.5	4L274	-1	1.16	0.65	1.81	18	-1	
79X16	642	642.5	0.5	4C89	-1	2.56	1.75	4.31	36	-1	
79X16	642.5	644.1	1.6	4A47	-1	1.74	2.22	3.96	24	-1	
79X16	644.1	645.1	1	4E19	-1	1.78	0.38	2.16	35	-1	
79X16	645.1	647.9	2.8	4L37	-1	0.51	0.34	0.85	10	-1	
79X16	647.9	649.1	1.2	4L294	-1	1.57	1.63	3.2	26	-1	
79X16	649.1	651.1	2	4C294	-1	1.36	0.69	2.05	23	-1	
79X16	651.1	652.1	1	4C294	-1	1.71	1.48	3.19	25	-1	
79X16	652.1	655	2.9	4L482	-1	1.33	0.83	2.16	18	-1	
79X16	655	656.8	1.8	4L7	-1	0.74	0.54	1.28	9	-1	
79X16	656.8	687.3	30.5	WASTE	-1	-1	-1	-1	-1	-1	
79X16	687.3	687.5	0.2	4A79	-1	1.54	1.13	2.67	26	-1	
79X16	687.5	689.6	2.1	4G49	-1	5.1	4.64	9.74	67	-1	
79X16	689.6	691.6	2	4L37	-1	0.03	0.04	0.07	2	-1	
79X16	691.6	693.6	2	4L37	-1	0.02	0.02	0.04	2	-1	
79X16	693.6	694.9	1.3	4L37	-1	0.04	0.03	0.07	1	-1	
79X16	694.9	696.9	2	4L7	-1	0.08	0.04	0.12	1	-1	
79X16	696.9	710.8	13.9	WASTE	-1	-1	-1	-1	-1	-1	
79X16	710.8	712.1	1.3	4L3	-1	0.07	0.06	0.13	1	-1	
79X16	712.1	714.3	2.2	4C0	-1	1.43	4.56	5.99	15	-1	
79X16	714.3	715.7	1.4	4L3	-1	0.09	0.21	0.3	0.1	-1	
79X16	715.7	716.9	1.2	4C7	-1	0.07	0.04	0.11	0.1	-1	
79X16	716.9	719.9	3	4L3	-1	0.1	0.21	0.31	0.1	-1	
79X16	719.9	721.1	1.2	4C9	-1	1.31	4.61	5.92	18	-1	
79X16	721.1	722.3	1.2	4E9	-1	0.9	0.63	1.53	13	-1	
79X16	722.3	732.5	10.2	WASTE	-1	-1	-1	-1	-1	-1	
79X16	732.5	734	1.5	4A0	-1	0.2	0.34	0.54	4	-1	
79X16	734	735.1	1.1	4C9	-1	0.94	0.31	1.25	11	-1	
79X16	735.1	735.4	0.3	4L0	-1	0.09	0.07	0.16	0.1	-1	
79X16	735.4	735.7	0.3	4C9	-1	1.39	0.47	1.86	17	-1	
79X16	735.7	805	69.3	WASTE	-1	-1	-1	-1	-1	-1	
79X16	805	805.3	0.3	4G4	-1	6.8	9.78	16.58	90	-1	
79X16	805.3	805.7	0.4	4K0	-1	0.26	0.01	0.27	4	-1	
79X16	805.7	806.8	1.1	5B0	-1	0.13	0.14	0.27	0.1	-1	
79X16	806.8	808.6	1.8	4K19	-1	1.57	0.34	1.91	19	-1	
79X16	808.6	809.1	0.5	4G4	-1	6.34	8.41	14.75	70	-1	7.375
79X16	809.1	811.5	2.4	4C9	-1	2.04	1.33	3.37	33	-1	8.088
79X16	811.5	811.8	0.3	4G4	4.37	7.07	9.86	16.93	124	0.88	5.079
79X16	811.8	812.5	0.7	4E0	4.36	6	8.18	14.18	84	1.65	9.926
79X16	812.5	812.9	0.4	4G0	3.6	4.55	7.31	11.86	69	0.62	4.744
79X16	812.9	814.4	1.5	4G4	4.28	7.55	8.18	15.73	119	1.44	23.595
79X16	814.4	815.5	1.1	4D4	3.96	6.26	8.79	15.05	87	1.06	16.555
79X16	815.5	816.4	0.9	4G4	3.69	8.51	6.5	15.01	104	0.88	13.509
79X16	816.4	817.8	1.4	4D4	4.15	6.5	5.8	12.3	80	0.88	17.22
79X16	817.8	819.9	2.1	4G4	4.55	5.15	8.06	13.21	94	0.58	27.741
79X16	819.9	820.2	0.3	4H9	3.86	3.8	5.16	8.96	58	0.41	2.688
79X16	820.2	830.6	10.4	WASTE	-1	-1	-1	-1	-1	-1	136.52
79X16	830.6	832.7	2.1	4L42	-1	1.4	1.73	3.13	26	-1	11.6
79X16	832.7	833.9	1.2	4L3	-1	1.24	1.84	3.08	25	-1	
79X16	833.9	836.9	3	WASTE	-1	-1	-1	-1	-1	-1	
79X16	836.9	837.2	0.3	4E7	-1	4.22	6.27	10.49	139	-1	



BY PROPERTY  
LENGTH WEIGHTED GRADE CALC'S

File: ASSYDAT.WR1

HOLE-ID	FROM (m)	TO (m)	INTERVAL	ROCK CODE	SG-PULP	Pb%	Zn%	Pb+Zn%	Ag(g/t)	Au(g/t)		
79X17	526.8	527.9	1.1	4H4	3.92	3.73	6.83	10.56	68	0.27	11.616	
79X17	527.9	529.2	1.3	4G4	4.17	2.27	7.16	9.43	39	0.31	12.259	
79X17	529.2	530	0.8	4H4	4.37	1.32	3.05	4.37	23	0.17	3.496	
79X17	530	531.3	1.3	4G0	4.42	1.88	5.41	7.29	20	0.21	9.477	
79X17	531.3	533	1.7	4H0	-1	0.87	1.74	2.61	17	-1	4.437	
											-----	
79X17	533	669.6	136.6	WASTE	-1	-1	-1	-1	-1	-1	41.285	6.2

6.66% /6.2m

BY PROPERTY  
LENGTH WEIGHTED GRADE CALC'S

File: ASSYDAT.WR1

HOLE-ID	FROM (m)	TO (m)	INTERVAL	ROCK CODE	SG-PULP	Pb%	Zn%	Pb+Zn%	Ag(g/t)	Au(g/t)		
79X18	627.1	629.1	2	4L73	-1	0.03	0.01	0.04	1	-1		
79X18	629.1	631.1	2	4L73	-1	0.06	0.02	0.08	1	-1		
79X18	631.1	633.9	2.8	4L73	-1	0.2	0.16	0.36	3	-1		
79X18	633.9	634.2	0.3	4C7	-1	1.45	1.18	2.63	16	-1		
79X18	634.2	634.9	0.7	4C789	-1	3.04	1.41	4.45	38	-1		
79X18	634.9	637.1	2.2	4C89	-1	2.18	1.53	3.71	37	-1		
79X18	637.1	637.6	0.5	4E9	-1	1.27	1.34	2.61	26	-1		
79X18	637.6	638.2	0.6	4G49	-1	4.34	6.71	11.05	80	-1		
79X18	638.2	638.8	0.6	4C89	-1	0.52	0.19	0.71	18	-1		
79X18	638.8	639.4	0.6	4E89	-1	0.27	0.2	0.47	19	-1		
79X18	639.4	640.4	1	4A9	-1	0.24	0.13	0.37	9	-1		
79X18	640.4	643.1	2.7	4C79	-1	0.21	0.22	0.43	10	-1		
79X18	643.1	645.1	2	4C79	-1	0.24	0.16	0.4	9	-1		
79X18	645.1	647.1	2	4C79	-1	0.11	0.04	0.15	10	-1		
79X18	647.1	649.1	2	4C79	-1	0.1	0.04	0.14	6	-1		
79X18	649.1	651.1	2	4C7	-1	0.06	0.02	0.08	3	-1		
79X18	651.1	651.5	0.4	4A0	-1	0.13	0.02	0.15	3	-1		
79X18	651.5	653.5	2	4L7	-1	0.06	0.06	0.12	0.1	-1		
79X18	653.5	654.4	0.9	4L7	-1	0.23	0.13	0.36	0.1	-1		
79X18	654.4	654.8	0.4	4D4	-1	7.94	7.22	15.16	75	-1	6.064	
79X18	654.8	656.2	1.4	4G0	-1	3.6	4.55	8.15	52	-1	11.41	
79X18	656.2	656.8	0.6	4H4	-1	1.74	1.31	3.05	22	-1	1.83	
79X18	656.8	657.5	0.7	4H49	-1	2	1.45	3.45	35	-1	2.415	7.01% /3.1m
79X18	657.5	658.1	0.6	4C89	-1	0.74	0.13	0.87	13	-1	21.719	3.1
79X18	658.1	658.5	0.4	4G4	-1	1.41	0.96	2.37	20	-1		
79X18	658.5	659.4	0.9	4C9	-1	0.6	0.18	0.78	21	-1		
79X18	659.4	659.9	0.5	4G4	-1	2.89	7.14	10.03	41	-1	5.015	
79X18	659.9	660.8	0.9	5D0	-1	0.24	0.32	0.56	3	-1	0.504	
79X18	660.8	662.3	1.5	4G4	-1	4.59	7.39	11.98	61	-1	17.97	8.10% /2.9m
											23.489	2.9
79X18	662.3	662.8	0.5	4E1	-1	1.85	2.4	4.25	64	-1	2.125	
79X18	662.8	663.4	0.6	4A4	-1	1.43	2.76	4.19	32	-1	2.514	
79X18	663.4	663.7	0.3	4D0	-1	4.04	0.6	4.64	48	-1	1.392	4.31% /1.4m
79X18	663.7	665.7	2	4A0	-1	4.78	1.96	6.74	47	-1		
79X18	665.7	668.5	2.8	4A0	-1	4.43	0.71	5.14	40	-1	6.031	1.4
79X18	668.5	670.5	2	4C0	-1	0.11	0.09	0.2	8	-1		
79X18	670.5	671.7	1.2	4C0	-1	0.25	0.37	0.62	7	-1		
79X18	671.7	694.4	22.7	WASTE	-1	-1	-1	-1	-1	-1		
79X18	694.4	694.9	0.5	4L39	-1	0.37	0.31	0.68	5	-1		
79X18	694.9	695.4	0.5	4E9	-1	1.56	1.36	2.92	19	-1		
79X18	695.4	738	42.6	WASTE	-1	-1	-1	-1	-1	-1		
79X18	738	738.6	0.6	4A4	2.83	2.98	6.97	9.95	55	0.38	5.97	
79X18	738.6	740.5	1.9	4D0	3.62	2.57	3.66	6.23	86	2.02	11.837	
79X18	740.5	741.2	0.7	4E19	4.06	3.17	4.44	7.61	109	0.47	5.327	
79X18	741.2	741.9	0.7	4G0	3.85	5.5	11.44	16.94	127	1.37	11.858	
79X18	741.9	743.9	2	4A4	2.88	2.27	6.21	8.48	45	0.75	16.96	
79X18	743.9	744.8	0.9	4A4	2.74	2.48	4.69	7.17	43	0.99	6.453	



BY PROPERTY  
LENGTH WEIGHTED GRADE CALC'S

File: ASSYDAT.WR1

HOLE-ID	FROM (m)	TO (m)	INTERVAL	ROCK CODE	SG-PULP	Pb%	Zn%	Pb+Zn%	Ag(g/t)	Au(g/t)		
80X01	710.6	710.9	0.3	4H0	-1	2.15	1.37	3.52	29	-1		
80X01	710.9	711.1	0.2	WASTE	-1	-1	-1	-1	-1	-1		
80X01	711.1	712.1	1	4G489	-1	3.2	2.36	5.56	48	-1		5.56
80X01	712.1	713.3	1.2	4G9	-1	2.94	2.62	5.56	41	-1		6.672
80X01	713.3	714.6	1.3	4G9	-1	2.31	1.83	4.14	32	-1		5.382
80X01	714.6	717	2.4	4A0	-1	1.38	1.95	3.33	25	-1		7.992
80X01	717	719	2	4G89	-1	4.04	3.94	7.98	56	-1		15.96
80X01	719	721.2	2.2	4G89	-1	2.92	2.28	5.2	46	-1		11.44
											5.25% /10.1m	
80X01	721.2	722.6	1.4	WASTE	-1	-1	-1	-1	-1	-1	53.006	10.1
80X01	722.6	724.5	1.9	4L74	-1	0.56	0.88	1.44	6	-1		
80X01	724.5	724.8	0.3	4E89	-1	2.29	1.68	3.97	29	-1		
80X01	724.8	757.3	32.5	WASTE	-1	-1	-1	-1	-1	-1		
80X01	757.3	758.8	1.5	4G34	4.46	7.1	7.78	14.88	102	1.1	22.32	
80X01	758.8	759.6	0.8	4K9	4.39	3.77	3.28	7.05	50	1.37	5.64	
80X01	759.6	761.6	2	4K4	4.18	5.98	5.12	11.1	76	1.1	22.2	
80X01	761.6	762.6	1	4C9	-1	0.43	0.48	0.91	16	-1	0.91	
80X01	762.6	764.2	1.6	4A7	-1	0.33	0.49	0.82	9	-1	1.312	
80X01	764.2	766.4	2.2	4K9	-1	1.2	0.72	1.92	18	-1	4.224	
80X01	766.4	766.8	0.4	4E4	3.76	5.15	8.57	13.72	62	1.17	5.488	
80X01	766.8	767.8	1	4K9	4.02	3.54	1.53	5.07	42	0.93	5.07	
80X01	767.8	768.3	0.5	4D6	3.78	4.72	9.43	14.15	64	0.82	7.075	
80X01	768.3	769.4	1.1	4E9	-1	2.02	2.54	4.56	48	-1	5.016	6.55% /12.1m
											79.255	12.1
80X01	769.4	771.1	1.7	4E9	-1	0.44	0.46	0.9	28	-1		
80X01	771.1	798.4	27.3	WASTE	-1	-1	-1	-1	-1	-1		
80X01	798.4	799.3	0.9	4K4	-1	2.36	2.98	5.34	49	-1	4.806	
80X01	799.3	799.8	0.5	4G4	-1	2.93	5.21	8.14	59	-1	4.07	
80X01	799.8	801.4	1.6	4K846	-1	2.52	1.94	4.46	41	-1	7.136	
80X01	801.4	803.4	2	4K846	-1	2.95	2.74	5.69	40	-1	11.38	5.48% /5.0m
											27.392	5.0
80X01	803.4	805	1.6	4K869	-1	0.92	0.34	1.26	29	-1		
80X01	805	806.3	1.3	4K6	-1	0.45	0.18	0.63	19	-1		
80X01	806.3	807.7	1.4	4K6	-1	0.29	0.12	0.41	20	-1		
80X01	807.7	809.4	1.7	4K869	-1	0.47	0.17	0.64	16	-1		
80X01	809.4	811.1	1.7	4K869	-1	2.48	1.34	3.82	40	-1		
80X01	811.1	812.9	1.8	4K869	-1	1.54	0.93	2.47	20	-1		
80X01	812.9	837.4	24.5	WASTE	-1	-1	-1	-1	-1	-1		
80X01	837.4	837.7	0.3	4E48	-1	2.89	2.3	5.19	41	-1		
80X01	837.7	838.8	1.1	WASTE	-1	-1	-1	-1	-1	-1		
80X01	838.8	839.7	0.9	4G4	-1	1.16	0.83	1.99	23	-1		
80X01	839.7	840.4	0.7	4K0	-1	2.84	4.5	7.34	46	-1		
80X01	840.4	841.7	1.3	4E89	-1	1.18	2.14	3.32	23	-1		
80X01	841.7	842.6	0.9	4C9	-1	0.9	0.44	1.34	25	-1		
80X01	842.6	861.4	18.8	WASTE	-1	-1	-1	-1	-1	-1		
80X01	861.4	862.2	0.8	4K9	-1	0.29	0.08	0.37	13	-1		
80X01	862.2	862.8	0.6	4K4	-1	0.41	0.46	0.87	12	-1		
80X01	862.8	863.1	0.3	4A4	-1	3.46	5.81	9.27	57	-1		
80X01	863.1	879.2	16.1	WASTE	-1	-1	-1	-1	-1	-1		
80X01	879.2	880.5	1.3	4K4	-1	1.92	1.3	3.22	25	-1		

BY PROPERTY  
LENGTH WEIGHTED GRADE CALC'S

File: ASSYDAT.WR1

BOX01	880.5	955.5	75 WASTE	-1	-1	-1	-1	-1	-1
-------	-------	-------	----------	----	----	----	----	----	----

DY PROPERTY  
LENGTH WEIGHTED GRADE CALC'S

File: ASSYDAT.WR1

HOLE-ID	FROM (m)	TO (m)	INTERVAL		SG-PULP	Pb%	Zn%	Pb+Zn%	Ag(g/t)	Au(g/t)		
80X02	731.9	733.3	1.4	4H34	-1	2.71	2.81	5.52	37	-1		
80X02	733.3	783.6	50.3	WASTE	-1	-1	-1	-1	-1	-1		
80X02	783.6	784.7	1.1	4F9	-1	0.05	0.77	0.82	5	-1		
80X02	784.7	827.8	43.1	WASTE	-1	-1	-1	-1	-1	-1		
80X02	827.8	829.5	1.7	4E489	-1	3.84	3.11	6.95	51	-1		
80X02	829.5	831.1	1.6	4E489	-1	2.02	1.98	4	24	-1		
80X02	831.1	833	1.9	4G429	4.51	9.55	10.14	19.69	90	1.7	37.411	
80X02	833	835	2	4G42	4.46	8.82	10.24	19.06	106	1.17	38.12	
80X02	835	837.2	2.2	4G42	4.47	8.26	9.45	17.71	108	0.82	38.962	
80X02	837.2	839	1.8	4A4	2.8	2.5	5.66	8.16	40	0.27	14.688	
80X02	839	841	2	4A4	2.72	2.04	5.69	7.73	38	0.34	15.46	
80X02	841	843	2	4A4	-1	1.44	2.76	4.2	23	-1	8.4	
80X02	843	845	2	4A4	-1	2.12	3.99	6.11	32	-1	12.22	
80X02	845	847	2	4A4	-1	2.04	2.98	5.02	27	-1	10.04	
80X02	847	848.2	1.2	4A4	-1	1.27	3.32	4.59	22	-1	5.508	
80X02	848.2	850.3	2.1	4A4	-1	2	4.8	6.8	32	-1	14.28	
80X02	850.3	852.1	1.8	4A4	-1	1.8	3.84	5.64	27	-1	10.152	
80X02	852.1	854.3	2.2	4A4	-1	1.49	3.22	4.71	23	-1	10.362	
80X02	854.3	855.9	1.6	4A4	-1	2.14	3.76	5.9	33	-1	9.44	9.07% /24.8m
80X02	855.9	857.9	2	4A0	-1	0.91	1.63	2.54	13	-1	225.043	24.8
80X02	857.9	859.9	2	4A0	-1	0.77	1.28	2.05	10	-1		
80X02	859.9	862	2.1	4A0	-1	0.63	0.89	1.52	11	-1		
80X02	862	862.8	0.8	4A0	-1	0.83	1.28	2.11	9	-1		
80X02	862.8	864.8	2	4A4	-1	0.77	1.34	2.11	10	-1		
80X02	864.8	866.8	2	4A4	-1	1.76	3.21	4.97	23	-1		
80X02	866.8	868.7	1.9	4A4	-1	2.19	3.65	5.84	26	-1		
80X02	868.7	872.7	4	WASTE	-1	-1	-1	-1	-1	-1		
80X02	872.7	874	1.3	4G0	-1	4	6.16	10.16	65	-1		
80X02	874	876.8	2.8	WASTE	-1	-1	-1	-1	-1	-1		
80X02	876.8	879.2	2.4	4A4	-1	2.56	2.73	5.29	50	-1		
80X02	879.2	880.1	0.9	WASTE	-1	-1	-1	-1	-1	-1		
80X02	880.1	882.3	2.2	4A0	-1	0.51	0.46	0.97	11	-1		
80X02	882.3	883.1	0.8	WASTE	-1	-1	-1	-1	-1	-1		
80X02	883.1	883.5	0.4	4A49	-1	0.87	1.07	1.94	20	-1		
80X02	883.5	883.8	0.3	WASTE	-1	-1	-1	-1	-1	-1		
80X02	883.8	886	2.2	4A4	-1	2.89	5.26	8.15	49	-1	17.93	
80X02	886	887.5	1.5	4A4	-1	2.51	3.68	6.19	42	-1	9.285	
80X02	887.5	888.9	1.4	4A4	-1	1.73	1.64	3.37	32	-1	4.718	
80X02	888.9	890.8	1.9	4G4	4.27	4.28	8.13	12.41	82	1.51	23.579	
80X02	890.8	891.8	1	4E4	4.2	6.53	13.91	20.44	98	1.37	20.44	
80X02	891.8	893.4	1.6	4G42	4.55	4.26	8.17	12.43	78	0.75	19.888	
80X02	893.4	895.4	2	4E0	4.58	3.48	6.47	9.95	58	1.92	19.9	
80X02	895.4	897.4	2	4E9	-1	1.2	1.48	2.68	27	-1	5.36	
80X02	897.4	899.1	1.7	4E9	-1	0.3	0.51	0.81	11	-1	1.377	
80X02	899.1	900.6	1.5	4E0	-1	2.92	2.82	5.74	43	-1	8.61	
80X02	900.6	902.6	2	4D9	3.88	3.62	8.4	12.02	68	0.69	24.04	
80X02	902.6	904.9	2.3	4D9	3.66	5.84	11.09	16.93	100	1.7	38.939	9.20% /21.1m
80X02	904.9	906.9	2	4C9	-1	0.21	0.4	0.61	10	-1	194.066	21.1
80X02	906.9	908.4	1.5	4C9	-1	0.52	0.8	1.32	21	-1		
80X02	908.4	910.1	1.7	4C9	-1	2.38	0.23	2.61	20	-1		

BY PROPERTY  
LENGTH WEIGHTED GRADE CALC'S

File: ASSYDAT.WR1

80X02	910.1	921.9	11.8	WASTE	-1	-1	-1	-1	-1	-1
-------	-------	-------	------	-------	----	----	----	----	----	----

DY PROPERTY  
LENGTH WEIGHTED GRADE CALC'S

File: ASSYDAT.WR1

HOLE-ID	FROM (m)	TO (m)	INTERVAL	ROCK CODE	SG-PULP	Pb%	Zn%	Pb+Zn%	Ag(g/t)	Au(g/t)
80X03	543	543.8	0.8	4E0	-1	2.38	3.44	5.82	45	-1
80X03	543.8	955.5	411.7	WASTE	-1	-1	-1	-1	-1	-1

DY PROPERTY  
LENGTH WEIGHTED GRADE CALC'S

File: ASSYDAT.WR1

HOLE-ID	FROM (m)	TO (m)	INTERVAL	ROCK CODE	SG-PULP	Pb%	Zn%	Pb+Zn%	Ag(g/t)	Au(g/t)
80X04	802.7	803.6	0.9	4E189	-1	0.98	0.5	1.48	20	-1
80X04	803.6	803.9	0.3	4G4	-1	3.75	2.72	6.47	46	-1
80X04	803.9	804.3	0.4	4C79	-1	1.85	2.76	4.61	37	-1
80X04	804.3	806.7	2.4	4A0	-1	1.46	1.45	2.91	24	-1
80X04	806.7	808.4	1.7	4A0	-1	0.9	0.97	1.87	52	-1
80X04	808.4	810.4	2	4G9	5.21	7.38	9.3	16.68	112	1.37
80X04	810.4	811.4	1	4E89	4.57	0.56	0.49	1.05	19	2.09
80X04	811.4	811.8	0.4	4G4	4.42	7.19	9.52	16.71	106	1.37
80X04	811.8	819.4	7.6	WASTE	-1	-1	-1	-1	-1	-1
80X04	819.4	821.4	2	4L7	-1	0.04	0.04	0.08	1	-1
80X04	821.4	823.4	2	4L7	-1	0.17	0.09	0.26	1	-1
80X04	823.4	825.4	2	4L7	-1	0.39	0.24	0.63	1	-1
80X04	825.4	827.4	2	4L7	-1	0.03	0.04	0.07	1	-1
80X04	827.4	829.4	2	4L7	-1	0.02	0.02	0.04	1	-1
80X04	829.4	831.2	1.8	4L7	-1	0.02	0.02	0.04	1	-1
80X04	831.2	892.7	61.5	WASTE	-1	-1	-1	-1	-1	-1
80X04	892.7	893.4	0.7	4C0	-1	0.22	0.08	0.3	5	-1
80X04	893.4	895.3	1.9	4A0	-1	0.72	0.94	1.66	10	-1
80X04	895.3	895.5	0.2	4E0	-1	1.39	1.32	2.71	36	-1
80X04	895.5	897.7	2.2	4G9	-1	2.75	1.92	4.67	40	-1
80X04	897.7	932.9	35.2	WASTE	-1	-1	-1	-1	-1	-1
80X04	932.9	933.4	0.5	4A4	-1	2.72	3.95	6.67	43	-1
80X04	933.4	933.7	0.3	4E4	-1	6.04	6.35	12.39	78	-1
80X04	933.7	934.3	0.6	4A9	-1	0.5	1.29	1.79	8	-1
80X04	934.3	936.2	1.9	4C79	-1	0.27	0.41	0.68	7	-1
80X04	936.2	937.6	1.4	4C7	-1	1.49	1.33	2.82	22	-1
80X04	937.6	939	1.4	4C7	-1	1.09	0.98	2.07	14	-1
80X04	939	1009.1	70.1	WASTE	-1	-1	-1	-1	-1	-1



DY PROPERTY  
LENGTH WEIGHTED GRADE CALC'S

File: ASSYDAT.WR1

HOLE-ID	FROM (m)	TO (m)	INTERVAL	ROCK CODE	SG-PULF	Pb%	Zn%	Pb+Zn%	Ag(g/t)	Au(g/t)		
BOX06	842	842.5	0.5	4H9	-1	0.35	0.23	0.58	6	-1		
BOX06	842.5	844.5	2	4G89	-1	2.93	2.84	5.77	42	-1	11.54	
BOX06	844.5	846.5	2	4G89	-1	4.61	5.45	10.06	67	-1	20.12	
BOX06	846.5	848.7	2.2	4G89	-1	4.71	4.63	9.34	66	-1	20.548	
BOX06	848.7	850.6	1.9	4A0	-1	1.63	1.45	3.08	24	-1	5.852	7.17% /8.1m
BOX06	850.6	852.5	1.9	WASTE	-1	-1	-1	-1	-1	-1	58.06	8.1
BOX06	852.5	854.5	2	4L7	-1	0.01	0.01	0.02	2	-1		
BOX06	854.5	856.5	2	4L7	-1	0.01	0.01	0.02	1	-1		
BOX06	856.5	858.5	2	4L7	-1	0.15	0.12	0.27	3	-1		
BOX06	858.5	860.5	2	4L7	-1	0.08	0.86	0.94	2	-1		
BOX06	860.5	861.9	1.4	4L7	-1	0.04	0.06	0.1	0.5	-1		
BOX06	861.9	862.7	0.8	4L3	-1	0.22	0.41	0.63	2	-1		
BOX06	862.7	863.2	0.5	4D46	4.19	4.14	6.11	10.25	59	0.55	5.125	
BOX06	863.2	863.7	0.5	4B4	4.86	4.75	6.65	11.4	64	0.62	5.7	
BOX06	863.7	864.7	1	4A0	-1	0.47	0.5	0.97	4	-1	0.97	
BOX06	864.7	867	2.3	4E49	-1	2.96	2.51	5.47	41	-1	12.581	
BOX06	867	868	1	4E89	-1	2.94	3.2	6.14	57	-1	6.14	
BOX06	868	868.5	0.5	4L0	-1	0.6	0.8	1.4	6	-1	0.7	
BOX06	868.5	870.2	1.7	4E9	-1	2.61	2.73	5.34	51	-1	9.078	
BOX06	870.2	870.5	0.3	4H9	-1	3.32	0.25	3.57	55	-1	1.071	5.30% /7.8m
BOX06	870.5	875	4.5	WASTE	-1	-1	-1	-1	-1	-1	41.365	7.8
BOX06	875	875.4	0.4	4G48	4.35	6.38	8.13	14.51	89	1.47	5.804	
BOX06	875.4	876.1	0.7	4E89	4.83	3.01	2.13	5.14	45	1.71	3.598	
BOX06	876.1	877.1	1	4G48	4.55	5.83	8.13	13.96	84	1.09	13.96	11.12% /2.1m
BOX06	877.1	877.5	0.4	4E89	-1	0.7	0.44	1.14	23	-1	23.362	2.1
BOX06	877.5	878.4	0.9	4C0	-1	0.76	1.2	1.96	11	-1		
BOX06	878.4	879.9	1.5	4A9	-1	1.15	1.05	2.2	21	-1		
BOX06	879.9	881.3	1.4	4D79	-1	1.65	2.17	3.82	23	-1		
BOX06	881.3	881.7	0.4	4G0	-1	2.38	4.15	6.53	36	-1	2.612	
BOX06	881.7	882.3	0.6	4D79	-1	0.61	1.25	1.86	8	-1	1.116	
BOX06	882.3	883.2	0.9	4E19	-1	1.36	2.02	3.38	19	-1	3.042	
BOX06	883.2	885.4	2.2	4D8	4.46	0.96	5.43	6.39	116	1.65	14.058	
BOX06	885.4	886.1	0.7	4E89	4.42	4.22	2	6.22	50	1.78	4.354	
BOX06	886.1	888.6	2.5	4G489	3.94	7.2	6.46	13.66	99	1.17	34.15	
BOX06	888.6	890.6	2	4E869	-1	1.99	1.65	3.64	30	-1	7.28	
BOX06	890.6	891.5	0.9	4E869	-1	0.3	0.45	0.75	13	-1	0.675	
BOX06	891.5	893	1.5	4C9	-1	2.19	2.14	4.33	37	-1	6.495	
BOX06	893	893.7	0.7	4G0	-1	5.29	3.72	9.01	81	-1	6.307	
BOX06	893.7	895.7	2	4E89	-1	0.57	0.86	1.43	12	-1	2.86	
BOX06	895.7	896.6	0.9	4E89	-1	0.77	0.82	1.59	22	-1	1.431	
BOX06	896.6	898.6	2	4C7	-1	3.37	1.42	4.79	45	-1	9.58	
BOX06	898.6	900.6	2	4C7	-1	0.9	2.04	2.94	10	-1	5.88	
BOX06	900.6	902.6	2	4C7	4.12	2.44	5.84	8.28	32	0.69	16.56	
BOX06	902.6	904.3	1.7	4C7	3.69	2.18	5.31	7.49	35	0.82	12.733	5.61% /23.0m





BY PROPERTY

LENGTH WEIGHTED GRADE CALC'S

File: ASSYDAT.WR1

ROCK

HOLE-ID FROM (m) TO (m) INTERVAL CODE SG-FULP PB% Zn% Pb+Zn% Ag(g/t) Au(g/t)

822.3	823	0.7	46489	-1	4.63	5.44	10.07	71	-1	7.049	822.3	80X08
826.5	826.5	3.5	4L679	-1	0.64	0.82	1.46	13	-1	5.11	826.5	80X08
827	827	0.5	46148	-1	4.32	5.35	9.67	62	-1	4.835	827	80X08
829.2	829.2	2.2	WASTE	-1	-1	-1	-1	-1	-1	16.994	829.2	80X08
829.7	829.7	0.5	464	3.9	3.79	5.35	9.14	75	1.51	4.57	829.7	80X08
830.5	830.5	0.8	4D469	4.43	5.16	5.14	10.3	64	0.69	8.24	830.5	80X08
831.4	831.4	0.9	460	4.29	7.05	6.92	13.97	83	0.93	12.573	831.4	80X08
831.9	831.9	0.5	4A97	3.1	0.45	0.74	1.19	9	0.75	0.595	831.9	80X08
832.9	832.9	1	464	4.35	7.26	10.56	17.82	108	1.17	17.82	832.9	80X08
834.4	834.4	1.5	4648	4.54	6.53	9.28	15.81	106	0.82	23.715	834.4	80X08
834.9	834.9	0.5	4E819	4.28	0.94	1.11	2.05	24	1.47	1.025	834.9	80X08
835.2	835.2	0.3	4C7	3.62	1.19	1.31	2.5	17	0.75	0.75	835.2	80X08
835.9	835.9	0.7	464	4.23	5.58	9.28	14.86	90	0.99	10.402	835.9	80X08
836.6	836.6	0.7	469	5.1	5.16	7.02	12.18	140	2.84	8.526	836.6	80X08
837.5	837.5	0.9	4E0	4.63	4.1	6.13	10.23	73	1.37	9.207	837.5	80X08
839.5	839.5	2	4641	4.51	7.16	9.19	16.35	99	0.55	32.7	839.5	80X08
841.1	841.1	1.6	464	4.75	10.1	9.77	19.87	138	0.75	31.792	841.1	80X08
841.8	841.8	0.7	4619	4.27	4.84	7.22	12.06	77	1.16	8.442	841.8	80X08
842.9	842.9	1.1	4C79	-1	1.49	1.76	3.25	31	-1	3.575	842.9	80X08
845.2	845.2	2.3	4E89	-1	0.69	0.84	1.53	18	-1	3.519	845.2	80X08
845.5	845.5	0.3	464	-1	5.26	7.12	12.38	88	-1	3.714	845.5	80X08
847	847	1.5	4E819	-1	1.46	1.61	3.07	34	-1	4.605	847	80X08
847.6	847.6	0.6	4C9	-1	1.8	1.6	3.4	33	-1	2.04	847.6	80X08
848.5	848.5	0.9	464	4.45	7.68	9.58	17.26	109	0.69	15.534	848.5	80X08
850.6	850.6	2.1	4E469	4.5	3.15	3.39	6.54	51	1.71	13.734	850.6	80X08
860.5	860.5	9.9	WASTE	-1	-1	-1	-1	-1	-1	217.078	860.5	80X08
861.5	861.5	1	464	4.25	5.42	8.2	13.62	83	0.69	13.62	861.5	80X08
863.5	863.5	2	4E189	4.15	2.39	2.32	4.71	49	1.54	9.42	863.5	80X08
865.1	865.1	1.6	4E189	3.86	4.18	3.87	8.05	51	1.3	12.88	865.1	80X08
865.8	865.8	0.7	460	4.39	7.69	8.5	16.19	82	1.51	11.333	865.8	80X08
866.5	866.5	0.7	4E89	-1	0.72	0.77	1.49	19	-1	1.043	866.5	80X08
867.8	867.8	1.3	4C79	-1	1.12	1.22	2.34	22	0.45	3.042	867.8	80X08
869.3	869.3	1.5	4E9	-1	1.28	1.72	3	31	1.03	4.5	869.3	80X08
869.9	869.9	0.6	464	8.14	8.52	16.66	16.66	147	0.38	9.996	869.9	80X08
871.9	871.9	2	4C7	-1	2.6	3.6	6.2	42	0.51	12.4	871.9	80X08
873.9	873.9	2	4C7	-1	2.69	1.58	4.27	38	0.65	8.54	873.9	80X08
874.9	874.9	1	4C79	-1	2	4.07	6.07	34	0.51	6.07	874.9	80X08
876.9	876.9	2	4C0	-1	0.96	1.29	2.25	24	1.65	4.5	876.9	80X08
878.9	878.9	2	4C89	-1	0.81	0.6	1.41	19	0.82	2.82	878.9	80X08
880.9	880.9	2	4C89	-1	2.74	3.67	6.41	46	0.62	12.82	880.9	80X08
882.9	882.9	2	4C89	-1	0.55	0.57	1.12	15	0.69	112.984	882.9	80X08
884.9	884.9	2	4C89	-1	0.37	1.14	1.51	6	0.48	0.48	884.9	80X08
886.9	886.9	2	4C89	-1	0.53	0.85	1.38	11	0.31	0.31	886.9	80X08
888.9	888.9	2	4C89	-1	0.36	0.47	0.83	12	0.65	0.65	888.9	80X08
890.3	890.3	1.4	4C89	-1	-1	-1	-1	-1	0.51	0.51	890.3	80X08
891	891	0.7	4C579	-1	0.21	0.23	0.44	10	0.55	0.55	891	80X08
893	893	2	4C79	-1	0.22	0.19	0.41	11	0.48	0.48	893	80X08
895	895	2	4C79	-1	0.18	0.25	0.43	12	0.55	0.55	895	80X08

5.54% / 20.4m

20.4

10.14% / 21.4m

21.4

4.7

3.62% / 4.7m





DY PROPERTY  
LENGTH WEIGHTED GRADE CALC'S

File: ASSYDAT.WR1

HOLE-ID	FROM (m)	TO (m)	INTERVAL	ROCK CODE	SG-FULP	Pb%	Zn%	Pb+Zn%	Ag(g/t)	Au(g/t)		
80X10	858.6	860.8	2.2	4H19	-1	3.24	3.95	7.19	63	-1		
80X10	860.8	862.4	1.6	4L17	-1	0.03	0.05	0.08	4	-1		
80X10	862.4	864.4	2	4L167	-1	0.26	0.21	0.47	5	-1		
80X10	864.4	866.4	2	4L167	-1	0.03	0.06	0.09	5	-1		
80X10	866.4	868.4	2	4L167	-1	0.04	0.11	0.15	1	-1		
80X10	868.4	870.4	2	4L167	-1	0.03	0.07	0.1	2	-1		
80X10	870.4	872.4	2	4L167	-1	0.02	0.06	0.08	3	-1		
80X10	872.4	874.4	2	WASTE	-1	-1	-1	-1	-1	-1		
80X10	874.4	876.9	2.5	4L167	-1	0.05	0.11	0.16	6	-1		
80X10	876.9	877.9	1	4L17	-1	0.07	0.12	0.19	5	-1		
80X10	877.9	879.8	1.9	4L13	-1	0.1	0.14	0.24	5	-1		
80X10	879.8	881.5	1.7	4A0	-1	2.31	3.19	5.5	27	-1	9.35	
80X10	881.5	881.8	0.3	4C0	-1	3.67	5.75	9.42	46	-1	2.826	6.09% /2.0m
80X10	881.8	909.8	28	WASTE	-1	-1	-1	-1	-1	-1	12.176	2.0
80X10	909.8	910.6	0.8	4G4		4.29	6.2	6.74	12.94	88	0.96	10.352
80X10	910.6	911.3	0.7	4E1		4.31	3.9	4.66	8.56	75	1.78	5.992
80X10	911.3	912.5	1.2	4G4		4.43	7.8	7.92	15.72	116	1.03	18.864
80X10	912.5	912.9	0.4	4K641		4.14	6.1	4.83	10.93	78	1.34	4.372
80X10	912.9	913.5	0.6	4G49		4.3	7.2	7.46	14.66	105	1.78	8.796
80X10	913.5	915.5	2	4G4		4.46	7.1	10.4	17.5	99	1.1	35
80X10	915.5	917.1	1.6	4G4		4.38	6.6	10.7	17.3	122	1.03	27.68
80X10	917.1	918.7	1.6	4E19		4.41	4.9	4.04	8.94	112	2.06	14.304
80X10	918.7	919.1	0.4	4G49		4.4	6.8	8.71	15.51	102	1.99	6.204
80X10	919.1	921.1	2	4E19		3.83	2.47	3.84	6.31	46	1.65	12.62
80X10	921.1	922.3	1.2	4E1		5.38	4.87	7.1	11.97	76	1.54	14.364
80X10	922.3	922.6	0.3	4G4		4.54	4.98	7.7	12.68	80	1.37	3.804
80X10	922.6	924.6	2	4E9		4.34	4.38	6.35	10.73	70	1.65	21.46
80X10	924.6	925.8	1.2	4E9		4.6	3.47	4.81	8.28	76	1.99	9.936
80X10	925.8	926.7	0.9	4D0		3.22	2.87	5.55	8.42	42	1.44	7.578
80X10	926.7	928.2	1.5	4A4		2.82	2.09	4.01	6.1	26	0.51	9.15
80X10	928.2	928.6	0.4	4G0		4.2	3.22	5.18	8.4	98	1.1	3.36
80X10	928.6	929	0.4	4K9	-1	0.14	0.08	0.22	15	-1	213.836	18.8
80X10	929	948.3	19.3	WASTE	-1	-1	-1	-1	-1	-1		
80X10	948.3	950.3	2	4A0	-1	0.59	1.42	2.01	12	-1		
80X10	950.3	950.8	0.5	4A0	-1	0.84	0.84	1.68	13	-1		
80X10	950.8	952.8	2	4G0	-1	1.83	3.07	4.9	30	-1	9.8	
80X10	952.8	954	1.2	4G9	-1	1.91	2.11	4.02	32	-1	4.824	
80X10	954	954.3	0.3	4A0	-1	0.84	2.05	2.89	12	-1	0.867	
80X10	954.3	955.3	1	4D0	-1	2.59	6.46	9.05	31	-1	9.05	
80X10	955.3	956.2	0.9	4A0	-1	1.99	3.55	5.54	24	-1	4.986	5.47% /5.4m
80X10	956.2	1040.2	84	WASTE	-1	-1	-1	-1	-1	-1	29.527	5.4





DY PROPERTY  
LENGTH WEIGHTED GRADE CALC'S

File: ASSYDAT.WR1

HOLE-ID	FROM (m)	TO (m)	INTERVAL	ROCK CODE	SG-PULP	Pb%	Zn%	Pb+Zn%	Ag(g/t)	Au(g/t)	
80X13	733.9	734.5	0.6	4E49	-1	3.85	4.55	8.4	63	-1	
80X13	734.5	735.7	1.2	4L74	-1	0.64	1.22	1.86	9	-1	
80X13	735.7	736.7	1	4E89	-1	2.1	2.59	4.69	36	-1	
80X13	736.7	738.7	2	4C79	-1	1.41	2.53	3.94	26	-1	
80X13	738.7	740.5	1.8	4C79	-1	1.66	2.19	3.85	33	-1	
80X13	740.5	742	1.5	4A7	-1	0.78	0.73	1.51	19	-1	
80X13	742	743.6	1.6	4C79	-1	1.6	2.75	4.35	24	-1	
80X13	743.6	743.9	0.3	4L9	-1	0.82	2.01	2.83	13	-1	
80X13	743.9	744.5	0.6	4D79	-1	3.13	5.67	8.8	36	-1	
80X13	744.5	745.3	0.8	4C89	-1	1.86	1.15	3.01	29	-1	
80X13	745.3	746.8	1.5	4C9	-1	0.55	1.44	1.99	11	-1	
80X13	746.8	747.5	0.7	WASTE	-1	-1	-1	-1	-1	-1	
80X13	747.5	748.9	1.4	4A7	-1	0.38	0.48	0.86	8	-1	
80X13	748.9	751	2.1	4C79	-1	0.2	0.18	0.38	6	-1	
80X13	751	753	2	4L127	-1	0.07	0.04	0.11	4	-1	
80X13	753	754.5	1.5	4L127	-1	0.09	0.05	0.14	4	-1	
80X13	754.5	782	27.5	WASTE	-1	-1	-1	-1	-1	-1	
80X13	782	783.5	1.5	4G48	4.51	5.05	7.52	12.57	64	0.58	18.855
80X13	783.5	785.5	2	4G189	4.26	3.46	4.38	7.84	48	0.86	15.68
80X13	785.5	786.7	1.2	4G189	4.41	3.48	5.67	9.15	46	0.58	10.98
80X13	786.7	788.7	2	4A0	3.03	3.55	3.84	7.39	46	0.58	14.78
80X13	788.7	790.7	2	4A0	-1	1.83	1.49	3.32	31	-1	6.64
80X13	790.7	792.7	2	4A0	-1	2.18	1.05	3.23	32	-1	6.46
80X13	792.7	794.9	2.2	4A0	-1	0.95	1.65	2.6	15	-1	5.72
80X13	794.9	795.6	0.7	4A4	-1	3.05	3.64	6.69	41	-1	4.683
80X13	795.6	796.1	0.5	4B0	-1	3.35	6.12	9.47	56	-1	4.735
80X13	796.1	797.9	1.8	4B8	-1	1.64	2.86	4.5	48	-1	8.1
80X13	797.9	799.5	1.6	4A4	-1	3.45	6.12	9.57	25	-1	15.312
80X13	799.5	801	1.5	4A0	-1	1.05	2.38	3.43	15	-1	5.145
80X13	801	914.7	113.7	WASTE	-1	-1	-1	-1	-1	-1	117.09
											19.0

6.16% /19.0m



DY PROPERTY  
LENGTH WEIGHTED GRADE CALC'S

File: ASSYDAT.WR1

HOLE-ID	FROM (m)	TO (m)	INTERVAL	ROCK CODE	SG-PULP	Pb%	Zn%	Pb+Zn%	Ag(g/t)	Au(g/t)		
EAB1X02	488.2	488.9	0.7	4L73	-1	0.23	0.19	0.42	4	-1		
EAB1X02	488.9	490.2	1.3	WASTE	-1	-1	-1	-1	-1	-1		
EAB1X02	490.2	490.6	0.4	4G0	-1	4.2	7.1	11.3	58	-1	4.52	
EAB1X02	490.6	491.2	0.6	4DK6	-1	4.3	7	11.3	49	-1	<del>6.78</del>	
EAB1X02	491.2	492.1	0.9	4C75	-1	3.3	2.02	5.32	30	-1	4.788	
EAB1X02	492.1	492.9	0.8	4A0	-1	3.2	2.3	5.5	29	-1	4.4	7.59% / 2.7m
EAB1X02	492.9	493.4	0.5	4C0	-1	0.15	0.04	0.19	32	-1	20.488	2.7
EAB1X02	493.4	494.1	0.7	4A0	-1	0.41	0.43	0.84	13	-1		
EAB1X02	494.1	496.1	2	4C07	-1	0.28	0.51	0.79	9	-1		
EAB1X02	496.1	497.9	1.8	4C07	-1	0.35	1.23	1.58	7	-1		
EAB1X02	497.9	500	2.1	4L32	-1	0.23	1.1	1.33	6	-1		
EAB1X02	500	500.3	0.3	4A7	-1	0.24	0.39	0.63	8	-1		
EAB1X02	500.3	513.7	13.4	WASTE	-1	-1	-1	-1	-1	-1		
EAB1X02	513.7	515.7	2	4C7	-1	0.98	0.41	1.39	19	-1		
EAB1X02	515.7	517.7	2	4C7	-1	0.03	0.06	0.09	5	-1		
EAB1X02	517.7	518.5	0.8	4C7	-1	0.09	0.24	0.33	7	-1		
EAB1X02	518.5	521.5	3	WASTE	-1	-1	-1	-1	-1	-1		
EAB1X02	521.5	523.5	2	4L7	-1	0.19	0.43	0.62	5	-1		
EAB1X02	523.5	525.1	1.6	4L7	-1	0.07	0.06	0.13	4	-1		
EAB1X02	525.1	562.5	37.4	WASTE	-1	-1	-1	-1	-1	-1		
EAB1X02	562.5	564.5	2	4L7	-1	0.02	0.03	0.05	6	-1		
EAB1X02	564.5	566.5	2	4L7	-1	0.01	0.02	0.03	4	-1		
EAB1X02	566.5	568.6	2.1	4L7	-1	0.04	0.01	0.05	4	-1		
EAB1X02	568.6	573.3	4.7	WASTE	-1	-1	-1	-1	-1	-1		
EAB1X02	573.3	574.8	1.5	4L24	-1	0.38	1.35	1.73	8	-1		
EAB1X02	574.8	576.8	2	4L16	-1	0.05	0.14	0.19	4	-1		
EAB1X02	576.8	578.8	2	4L16	-1	0.08	0.17	0.25	3	-1		
EAB1X02	578.8	580.3	1.5	4L16	-1	0.63	0.73	1.36	14	-1		
EAB1X02	580.3	590.4	10.1	WASTE	-1	-1	-1	-1	-1	-1		
EAB1X02	590.4	590.9	0.5	4G1	-1	4.6	4.6	9.2	36	-1		
EAB1X02	590.9	592.7	1.8	WASTE	-1	-1	-1	-1	-1	-1		
EAB1X02	592.7	592.9	0.2	4E1	-1	2.5	0.45	2.95	29	-1	0.59	
EAB1X02	592.9	593.5	0.6	4G4	-1	9.4	10.3	19.7	125	-1	11.82	
EAB1X02	593.5	593.7	0.2	4C0	-1	0.78	1.15	1.93	18	-1	0.386	12.80% / 1.0
EAB1X02	593.7	604.4	10.7	WASTE	-1	-1	-1	-1	-1	-1	12.796	1.0
EAB1X02	604.4	605.4	1	4E4	-1	8.9	10.2	19.1	146	-1		
EAB1X02	605.4	607.4	2	WASTE	-1	-1	-1	-1	-1	-1		
EAB1X02	607.4	607.8	0.4	4E41	-1	8.6	10.9	19.5	150	-1		
EAB1X02	607.8	828.1	220.3	WASTE	-1	-1	-1	-1	-1	-1		

1.0m / 11%

4.52  
~~6.78~~  
4.788  
4.4

7.59% / 2.7m

2.7

12.80% / 1.0

1.0

DY PROPERTY  
LENGTH WEIGHTED GRADE CALC'S

File: ASSYDAT.WR1

HOLE-ID	FROM (m)	TO (m)	INTERVAL	ROCK CODE	SG-PULP	Pb%	Zn%	Pb+Zn%	Ag(g/t)	Au(g/t)
EAB1X03	906.5	908.5	2	4L79	-1	2.73	1.46	4.19	44	-1
EAB1X03	908.5	919.5	11	WASTE	-1	-1	-1	-1	-1	-1
EAB1X03	919.5	920	0.5	4L7	-1	1.7	1.64	3.34	32	-1
EAB1X03	920	920.9	0.9	4E86	-1	3.56	1.67	5.23	59	-1
EAB1X03	920.9	922.1	1.2	4C7	-1	2.9	1.89	4.79	46	-1
EAB1X03	922.1	923.2	1.1	WASTE	-1	-1	-1	-1	-1	-1
EAB1X03	923.2	925.2	2	4A0	-1	1.06	0.71	1.77	20	-1
EAB1X03	925.2	927	1.8	4A0	-1	0.85	1.29	2.14	17	-1
EAB1X03	927	927.8	0.8	4A0	-1	0.37	0.15	0.52	11	-1
EAB1X03	927.8	931.3	3.5	WASTE	-1	-1	-1	-1	-1	-1
EAB1X03	931.3	931.7	0.4	4E86	-1	0.51	0.15	0.66	32	-1
EAB1X03	931.7	932.2	0.5	4G8	-1	0.92	0.65	1.57	26	-1
EAB1X03	932.2	934.2	2	4A0	-1	0.52	0.26	0.78	12	-1
EAB1X03	934.2	936.2	2	4A0	-1	0.32	0.05	0.37	9	-1
EAB1X03	936.2	936.9	0.7	4A0	-1	0.27	0.02	0.29	8	-1
EAB1X03	936.9	937.9	1	4L12	-1	0.18	0.49	0.67	13	-1
EAB1X03	937.9	941	3.1	WASTE	-1	-1	-1	-1	-1	-1
EAB1X03	941	941.7	0.7	4L17	-1	0.07	0.16	0.23	6	-1
EAB1X03	941.7	943.7	2	4L7	-1	0.02	0.03	0.05	4	-1
EAB1X03	943.7	945.7	2	4L7	-1	0.03	0.03	0.06	2	-1
EAB1X03	945.7	947.7	2	4L7	-1	0.02	0.02	0.04	2	-1
EAB1X03	947.7	949.7	2	4L7	-1	0.03	0.04	0.07	1	-1
EAB1X03	949.7	950.9	1.2	4L7	-1	0.01	0.02	0.03	1	-1
EAB1X03	950.9	951.2	0.3	4C5	-1	0.06	0.08	0.14	8	-1
EAB1X03	951.2	953.2	2	WASTE	-1	-1	-1	-1	-1	-1
EAB1X03	953.2	954.3	1.1	4C57	-1	0.77	0.68	1.45	13	-1
EAB1X03	954.3	956.7	2.4	4A0	-1	1.03	1.04	2.07	20	-1
EAB1X03	956.7	957.5	0.8	4A4	-1	2.92	4.03	6.95	54	-1
EAB1X03	957.5	958.2	0.7	4A0	-1	0.29	0.42	0.71	9	-1
EAB1X03	958.2	960.2	2	4G*	-1	2.17	2	4.17	51	-1
EAB1X03	960.2	961.8	1.6	4G*	-1	0.91	0.41	1.32	32	-1
EAB1X03	961.8	963.8	2	4C8	-1	0.27	0.12	0.39	20	-1
EAB1X03	963.8	964.7	0.9	4C8	-1	1.15	0.91	2.06	30	-1
EAB1X03	964.7	965.4	0.7	4E8	-1	2.55	1.58	4.13	41	-1
EAB1X03	965.4	966.2	0.8	4G8*	-1	4.7	3.28	7.98	55	-1
EAB1X03	966.2	966.7	0.5	4L1	-1	0.22	0.3	0.52	8	-1
EAB1X03	966.7	968.4	1.7	4G8*	-1	0.18	0.07	0.25	20	-1
EAB1X03	968.4	969.3	0.9	4E8	-1	0.25	0.13	0.38	30	-1
EAB1X03	969.3	971.3	2	4G8*	-1	3.38	1.87	5.25	49	-1
EAB1X03	971.3	973.3	2	4G8*	-1	3.28	3.21	6.49	46	-1
EAB1X03	973.3	973.6	0.3	4G8*	-1	2.08	2.36	4.44	35	-1
EAB1X03	973.6	975.6	2	4K68	-1	0.55	0.27	0.82	22	-1
EAB1X03	975.6	976.3	0.7	4K68	-1	1.75	1.34	3.09	37	-1
EAB1X03	976.3	977.8	1.5	4A0	-1	1.47	3.07	4.54	26	-1
EAB1X03	977.8	978.3	0.5	4E0	-1	0.1	0.14	0.24	14	-1
EAB1X03	978.3	1047.5	69.2	WASTE	-1	-1	-1	-1	-1	-1

DY PROPERTY  
LENGTH WEIGHTED GRADE CALC'S

File: ASSYDAT.WR1

HOLE-ID	FROM (m)	TO (m)	INTERVAL	SG-PULP	Pb%	Zn%	Pb+Zn%	Ag(g/t)	Au(g/t)
89DS-01	-1	-1		-1	-1	-1	-1	-1	-1
89DS-02	-1	-1		-1	-1	-1	-1	-1	-1