

017658

GRUM Assays  
(LISTING)

Numbers missing from 90000 series

inclusive

~~90116~~

FAGA 020

90128

90129

90130

90131

90132

90133

90167

90168

90169

90230

90<sup>23</sup>~~221~~

90312 - 90341

90354 - 90356

90359 - 90366

90378 - 90389

90454

90530 - 90533

90535

90958 - 90968

90988 - 90999

91067 - 91071

91080

91103

91611 - ~~91999~~ ~~92000~~ 91999

ALL ASSAYS - SAMPLE NUMBER

ODH	SAMPLE	---DEPTHS---		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAO	PB+ZN	PC+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGA153	1579	61.7	63.7	2.0	100	4AC	2.90	.08	.43	.40	7.0	.89				.83		.48
FAGA153	1580	63.7	65.7	2.0	100	4A0	2.98	.07	1.19	1.89	23.0	1.65				3.08		.61
FAGA153	1581	65.7	68.1	2.4	96	4AC	2.92	.09	.40	.27	7.0	1.51				.67		.40
FAGA153	1582	157.6	158.7	1.1	82	4A0	2.99	.14	.97	1.47	13.0	1.51	3.85	6.70		2.44	10.55	.60
FAGA153	1583	158.7	160.3	1.6	100	4A43	3.39	.14	2.04	4.65	41.0	1.37	1.58	16.40		6.69	17.98	.70
FAGA153	1584	160.3	162.1	1.8	78	4A43	3.63	.03	3.23	8.14	59.0	.48	1.89	18.20		11.37	20.09	.72
FAGA153	1585	162.1	162.9	.8	100	5B6	2.81	.01	.56	.83	9.0	.69	2.78	1.23		1.39	4.01	.60
FAGA153	1586	175.2	176.1	.9	89	4E64	4.43	.15	2.99	2.90	45.0	2.06	2.63	30.40		5.89	33.03	.49
FAGA153	1587	176.1	177.9	1.8	100	4G4	4.75	.17	9.45	8.74	106.0	.34	2.60	21.70		18.19	24.30	.48
FAGA153	1588	177.9	179.6	1.7	94	4G4	4.33	.06	5.04	7.43	75.0	.55	1.38	18.00		12.47	19.38	.60
FAGA153	1589	180.6	182.0	1.4	100	4E4	4.45	.20	6.27	5.22	75.0	.21	4.45	29.90		11.49	34.35	.45
FAGA153	1590	182.0	183.5	1.5	93	4E0	4.34	.20	1.14	.97	14.0	1.10	4.47	31.80		2.11	36.27	.46
FAGA153	1591	183.5	185.0	1.5	100	4K0	4.38	.26	1.99	1.81	27.0	1.23	5.20	31.20		3.80	36.40	.48
FAGA153	1592	185.0	186.5	1.5	93	4E84	4.33	.11	1.17	4.60	128.0	1.58	8.41	19.70		5.77	28.11	.80
FAGA153	1593	186.5	188.0	1.5	87	4G4	4.30	.06	4.12	7.30	66.0	.62	3.42	9.80		11.42	13.22	.64
FAGA153	1594	188.0	188.8	.8	100	4G4	3.04	.05	3.30	6.80	48.0	.69	1.69	8.00		10.10	9.69	.67
FAGA153	1595	188.8	190.3	1.5	100	4C3	3.61	.21	.50	.77	14.0	.89	4.05	21.90		1.27	25.95	.61
FAGA153	1596	190.3	191.8	1.5	93	4C3	3.46	.22	.77	1.07	12.0	.62	10.59	14.30		1.84	24.89	.58
FAGA153	1597	191.8	192.5	.7	100	4C3	3.74	.35	1.16	1.82	19.0	1.23	7.72	20.10		2.98	27.82	.61
FAGA153	1598	192.5	194.0	1.5	80	4C3	3.62	.30	2.00	.07	39.0	.69	4.10	21.80		2.07	25.90	.03
FAGA153	1599	194.0	197.0	3.0	90	4C3	3.45	.23	.58	.71	8.0	.75	8.68	14.40		1.29	23.08	.55
FAGA153	1600	197.0	199.9	2.9	86	4C3	3.71	.33	1.23	1.89	20.0	1.92	5.73	21.80		3.12	27.53	.61
FAGA153	1601	199.9	200.6	.7	43	4C3	3.32	.27	1.74	2.70	23.0	.69	3.96	12.50		4.44	16.46	.61
FAGA153	1602	200.6	201.8	1.2	83	4D3	3.34	.21	2.89	2.70	47.0	1.30	2.88	13.10		5.59	15.98	.48
FAGA153	1603	201.8	203.0	1.2	25	4C3	3.38	.08	.77	2.59	16.0	.34	8.77	13.50		3.36	22.27	.77
FAGA153	1604	203.0	206.0	3.0	100	4C7	3.49	.35	.96	1.15	19.0	.14	16.17	8.90		2.11	25.07	.55
FAGA153	1605	206.0	207.5	1.5	67	4C0	3.17	.27	.53	.58	9.0	.14	7.20	10.20		1.11	17.40	.52
FAGA153	1606	207.5	209.0	1.5	60	4C0	3.05	.11	1.87	1.22	30.0	.14	3.09	5.10		3.09	8.19	.39
FAGA153	1607	209.0	209.6	.6	50	4D3	3.68	.09	2.89	3.50	39.0	.21	6.19	18.30		6.39	24.49	.55
FAGA153	1608	209.6	210.9	1.3	100	4C3	3.24	.41	.78	.98	20.0	.48	4.62	13.40		1.76	18.02	.56
FAGA153	1609	210.9	212.4	1.5	100	4C0	3.21	.18	1.58	1.07	23.0	.27	3.38	11.40		2.65	14.78	.40
FAGA153	1610	212.4	214.0	1.6	87	4C7	3.13	.22	.46	.44	9.0	.07	6.07	7.60		.90	13.67	.49
FAGA045	1611	44.5	50.9	6.4	9	4B4	3.06	.12	4.63	7.23	67.0	.55	1.75	3.15		11.86	4.90	.61
FAGA045	1613	51.8	53.0	1.2	17	4B4	2.97	.04	2.64	5.83	37.0	.48	2.57	4.07		8.47	6.64	.69
FAGA045	1614	53.0	55.9	2.9	62	4B0	2.90	.03	1.96	5.15	37.0	.27	2.38	.98		7.11	3.36	.72
FAGA045	1615	55.9	57.9	2.0	75	4D0	3.67	.04	3.37	5.05	60.0	1.37	2.96	19.50		8.42	22.46	.60
FAGA045	1616	57.9	61.0	3.1	10	404	4.02	.06	4.51	12.90	72.0	1.17	5.24	18.90		17.41	24.14	.74
FAGA045	1617	61.0	61.9	.9		4D4	3.40	.04	7.52	5.05	105.0	1.37				12.57		.40
FAGA045	1618	64.2	66.4	2.2	95	4A4	3.56	.08	6.17	9.05	99.0	1.23				15.22		.59
FAGA045	1619	73.8	76.5	2.7	89	4A0	3.10	.10	.45	1.21	11.0	.48	1.21	13.90		1.66	15.11	.73
FAGA045	1620	76.5	77.7	1.2	100	4E4	4.62	.13	6.90	15.90	119.0	.48	5.82	24.90		22.80	30.72	.70
FAGA045	1621	77.7	79.2	1.5	93	4E0	4.38	.14	7.95	15.50	124.0	.48	3.78	22.90		23.45	26.68	.66
FAGA045	1622	79.2	81.1	1.9	79	4E4	4.80	.24	9.08	16.20	162.0	1.44	2.61	27.10		25.28	29.71	.64
FAGA045	1623	81.1	83.8	2.7	41	4E4	4.74	.18	9.49	16.80	157.0	1.03	3.44	26.50		26.29	29.94	.64
FAGA045	1624	83.8	84.4	.6	50	4E4	4.63	.13	7.73	16.20	165.0	.48	4.05	27.20		23.93	31.25	.68
FAGA045	1625	84.4	86.6	2.2	95	4A0	3.12	.11	1.42	2.41	17.0	.75	1.89	11.40		3.83	13.29	.63
FAGA045	1626	86.6	87.9	1.3	92	4A4	3.50	.12	3.05	5.73	64.0	1.03	1.68	16.40		8.78	18.08	.65
FAGA045	1627	166.1	167.8	1.7	18	G0UGE	2.79	.06	.19	.42	4.0	.27	2.20	5.50		.61	7.70	.69
FAGA045	1628	167.8	169.5	1.7	53	4A4	3.65	.14	2.99	5.09	42.0					8.08		.63
FAGA045	1629	169.5	171.3	1.8	94	4E1	2.85	.10	.22	.35	6.0	.27	2.27	7.40		.57	9.67	.61

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAO	PB+ZN	PO+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGA045	1630	171.3	172.8	1.5	100	4A0	2.84	.13	.73	2.29	16.0	.62	3.93	6.10		3.02	10.03	.76
FAGA045	1631	192.9	193.9	1.0	20	4D0	3.48	.02	2.66	3.87	78.0	.62	2.70	15.60		6.53	18.30	.59
FAGA045	1632	193.9	195.1	1.2	100	4G4	4.30	.09	6.79	8.53	125.0	1.44	.73	12.40		15.32	13.13	.56
FAGAC45	1633	195.1	196.6	1.5	60	4AL4	3.07	.06	2.62	3.34	40.0	.69	1.36	7.90		5.96	9.26	.56
FAGA045	1634	196.6	198.0	1.4	36	4G4	4.23	.18	5.32	8.27	99.0	1.65	1.53	18.20		13.59	19.73	.61
FAGA045	1635	199.0	201.2	2.2	100	4E1	4.29	.24	2.52	2.20	35.0	2.06	5.88	32.30		4.72	38.18	.47
FAGA045	1636	201.2	202.7	1.5	100	4E1	4.34	.24	1.81	.37	20.0	.96	7.91	31.00		2.18	38.91	.17
FAGA045	1637	202.7	204.2	1.5	100	4E18	4.30	.23	6.81	3.46	84.0	1.51	13.05	21.10		10.27	34.15	.34
FAGA045	1638	204.2	207.3	3.1	97	4EC	3.65	.30	1.07	.22	18.0	.55	3.49	22.40		1.29	25.89	.17
FAGA045	1639	207.3	208.8	1.5	100	4EC	3.57	.25	.38	.18	11.0	.48	2.52	23.10		.56	25.62	.32
FAGA045	1640	208.8	210.3	1.5	80	4EC	3.81	.21	1.20	1.10	20.0	1.78	4.06	25.10		2.30	29.16	.48
FAGA045	1641	210.3	210.9	.6	83	4EC	3.86	.32	2.17	1.08	33.0	1.30	10.43	19.90		3.25	30.33	.33
FAGA045	1642	210.9	212.4	1.5	100	4E1	4.31	.34	1.97	1.84	35.0	.65	6.03	29.50		3.81	35.53	.48
FAGA045	1643	212.4	213.1	.7	71	4A3	3.33	.23	1.40	2.51	22.0	.41	5.79	13.20		3.91	18.99	.64
FAGA143	1644	140.5	141.8	1.3	62	4L4	3.27	.03	3.78	7.10	59.0	.55	2.25	10.50		10.88	12.75	.65
FAGA143	1645	145.1	146.9	1.8	100	4E4	4.30	.04	4.09	5.73	87.0	.62	1.61	27.60		9.82	29.21	.58
FAGA143	1646	146.9	148.3	1.4	100	4A4	3.22	.11	1.87	3.29	30.0	.75	2.36	13.20		5.16	15.56	.64
FAGA205	1951	197.5	199.4	1.9	79	4D3	3.68	.23	4.00	4.50	49.0	.55				8.50		.53
FAGA205	1952	241.3	242.6	1.3	54	4CD	3.27	.12	3.00	4.40	48.0	.34	5.23	8.30		7.40	13.53	.59
FAGA205	1953	242.6	243.8	1.2	67	4L2	2.88	.07	.07	.18	1.0	.21	3.24	4.55		.25	7.79	.72
FAGA200	2051	72.5	73.9	1.4	86	4A0	3.21	.10	1.55	2.52	32.0	.82	.68	12.90		4.07	13.58	.62
FAGA200	2052	78.7	79.8	1.1	100	4A0	2.88	.10	.92	1.41	15.0	1.10				2.33		.61
FAGA200	2053	79.8	80.8	1.0	100	4A0	2.94	.08	1.45	1.81	20.0	.55				3.26		.56
FAGA200	2054	157.5	159.0	1.5	93	4A0	2.85	.09	.10	.39	4.0	.07				.49		.80
FAGA200	2055	159.0	160.5	1.5	87	4A0	2.81	.16	.01	.28	2.0	.34				.29		.97
FAGA200	2056	160.5	162.0	1.5	100	4A0	2.81	.06	.03	.05	2.0	.14				.08		.63
FAGA200	2057	162.0	163.5	1.5	93	4A0	2.86	.07	.06	.21	2.0	.14				.27		.78
FAGA200	2058	163.5	165.4	1.9	95	4A0	2.88	.10	.60	1.40	10.0	.62				2.00		.70
FAGA200	2059	167.2	168.9	1.7	94	4A0	2.88	.13	.12	.65	4.0	.27				.77		.84
FAGA200	2060	175.0	175.9	.9	100	4D47	4.03	.13	9.50	6.67	122.0	1.10	9.55	15.90		16.17	25.45	.41
FAGA200	2061	175.9	177.5	1.6	100	4AG	2.89	.02	1.60	2.36	23.0	.34	2.21	2.86		3.96	5.07	.60
FAGA200	2062	177.5	179.0	1.5	100	4A0	2.88	.02	.59	1.30	12.0	.41	.82	3.74		1.89	4.56	.69
FAGA200	2063	179.0	180.7	1.7	94	4AD	2.95	.22	2.12	3.91	33.0	.62	1.15	8.70		6.03	9.85	.65
FAGA200	2064	180.7	182.0	1.3	100	4G4	4.53	.07	9.30	9.66	120.0	.89	.67	12.20		18.96	12.87	.51
FAGA200	2065	182.0	183.2	1.2	100	4G4	4.56	.16	5.00	6.40	69.0	.83	1.71	20.00		11.40	21.71	.56
FAGA200	2066	183.2	184.7	1.5	100	4E84	4.55	.32	4.01	2.53	37.0	1.10	4.72	33.50		6.54	38.22	.39
FAGA200	2067	184.7	186.2	1.5	100	4E8	4.50	.42	1.41	.99	22.0	1.44	4.66	38.80		2.40	43.46	.41
FAGA200	2068	186.2	187.7	1.5	100	4E8	4.52	.42	1.45	1.41	24.0	1.44	7.49	35.50		2.86	42.99	.49
FAGA200	2069	187.7	189.2	1.5	100	4E8	4.59	.44	1.63	1.20	27.0	1.23	6.81	36.00		2.83	42.81	.42
FAGA200	2070	189.2	190.7	1.5	100	4E84	3.42	.15	4.70	10.13	76.0	.83	3.41	9.70		14.83	13.11	.68
FAGA200	2071	190.7	192.2	1.5	100	4E8	4.37	.34	1.15	1.46	25.0	1.10	9.36	33.00		2.61	42.36	.56
FAGA200	2072	192.2	193.7	1.5	100	4E8	4.79	.24	1.24	.91	15.0	1.23	5.05	30.90		2.15	35.95	.42
FAGA200	2073	193.7	195.0	1.3	100	4E8	3.95	.22	1.97	1.10	24.0	1.53	4.64	26.50		3.07	31.14	.36
FAGA200	2074	195.0	195.8	.8	100	4G4	4.17	.09	11.60	12.03	140.0	1.17	4.15	19.10		23.63	23.25	.51
FAGA200	2075	195.3	197.3	1.5	100	4D89	3.92	.18	2.19	3.86	34.0	.75	10.98	21.10		6.05	32.08	.64
FAGA200	2076	197.3	198.3	1.0	100	4C89	3.64	.31	1.06	1.98	17.0	.89	8.00	19.80		3.04	27.80	.65
FAGA200	2077	198.3	199.3	1.0	100	4C39	3.51	.38	.73	1.04	14.0	.75	3.16	22.00		1.77	25.16	.59
FAGA200	2078	199.3	200.3	1.0	100	4C39	3.30	.36	1.30	.14	20.0	.69	2.28	16.70		1.44	18.98	.10
FAGA200	2079	200.3	201.2	.9	89	4C3	3.43	.21	1.41	3.28	19.0	.27	.47	23.70		4.69	24.17	.70

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAO	PB+ZN	PO+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGA200	2080	201.2	202.7	1.5	100	4C89	3.89	.46	.25	.11	11.0	.69				.36		.31
FAGA200	2081	202.7	204.2	1.5	93	4C89	3.77	.27	.45	.38	11.0	.62				.83		.46
FAGA200	2082	204.2	205.3	1.1	100	4C89	3.70	.33	.66	.79	12.0	.55				1.45		.54
FAGA200	2083	205.3	206.0	.7	100	4C3	4.53	.39	.50	.71	18.0	1.51				1.21		.59
FAGA200	2084	208.2	209.7	1.5	100	4C38	3.76	.23	1.18	1.06	20.0	1.17	5.30	23.30		2.24	28.60	.47
FAGA200	2085	209.7	211.2	1.5	93	4C38	3.95	.24	1.51	2.44	26.0	1.17	12.50	22.10		3.95	34.60	.62
FAGA200	2086	211.2	212.2	1.0	100	4C38	4.46	.44	1.45	1.26	26.0	.89	6.73	34.90		2.71	41.63	.46
FAGA200	2087	212.2	213.1	.9	100	4G4	4.12	.19	4.64	6.85	71.0	.96	2.86	16.50		11.49	19.36	.60
FAGA200	2088	213.1	214.4	1.3	92	4ALDG	3.12	.02	2.12	3.93	32.0	.27	1.69	8.70		6.05	10.39	.65
FAGA200	2089	214.4	215.9	1.5	100	5D4*	2.91	.10	.73	.44	10.0	.07	4.59	3.02		1.17	7.61	.38
FAGA200	2090	215.9	217.4	1.5	100	5D4*	2.99	.08	.14	.33	5.0	.14				.47		.70
FAGA200	2091	219.6	221.1	1.5	100	4L2	2.81	.02	.03	.05	1.0	.07				.08		.63
FAGA200	2092	221.1	222.6	1.5	100	4L2	2.88	.03	.03	.03	1.0	.07				.06		.50
FAGA200	2093	222.6	224.1	1.5	100	4L2	2.92	.11	.04	.04	2.0	.14				.08		.50
FAGA200	2094	224.1	225.6	1.5	100	4L2	2.92	.25	.01	.01	3.0	.27				.02		.50
FAGA200	2095	225.6	227.0	1.4	100	4L2	2.93	.23	.01	.02	4.0	.21				.03		.67
FAGU003	2451	.0	1.0	1.0	50	4A1	3.05	.06	1.36	2.13	18.0	.69	.55	4.81		3.49	5.36	.61
FAGU003	2452	1.0	3.0	2.0	95	4A14	3.11	.04	3.39	6.01	46.0	.75	1.05	1.89		9.40	2.94	.64
FAGU003	2453	3.0	5.0	2.0	100	4A14	3.55	.06	4.03	5.83	46.0	.89	1.18	2.44		9.86	3.62	.59
FAGU003	2454	5.0	6.8	1.8	94	4A4	3.10	.05	4.65	6.20	61.0	.48	1.05	1.77		10.85	2.82	.57
FAGU003	2455	6.8	7.8	1.0	100	4AD	3.42	.14	4.40	5.92	73.0	1.23	1.27	15.82		10.32	17.09	.57
FAGU003	2456	7.8	8.8	1.0	100	4A14	3.79	.06	3.80	8.87	69.0	1.30	1.29	4.86		12.67	6.15	.70
FAGU003	2457	8.8	10.4	1.6	81	4C0	4.47	.16	1.62	1.27	44.0	1.71	.75	24.32		2.89	25.07	.44
FAGU003	2458	10.4	11.9	1.5	100	4C0	4.52	.19	1.27	1.63	35.0	2.06	.84	27.79		2.90	28.63	.56
FAGU003	2459	11.9	14.3	2.4	100	4CA	3.75	.16	1.34	1.96	31.0	1.59	.80	21.13		3.30	21.93	.59
FAGU003	2460	14.3	16.1	1.8	100	4E4	4.33	.10	9.35	17.70	167.0	1.37	1.55	21.40		27.05	22.95	.65
FAGU003	2461	42.7	43.7	1.0	100	4G42	3.49	.07	9.72	8.62	153.0	.75	2.94	11.67		18.34	14.61	.47
FAGU003	2462	43.7	45.6	1.9	100	4E4	4.96	.19	6.13	4.81	99.0	1.51	4.17	30.11		10.94	34.28	.44
FAGU003	2463	45.6	46.7	1.1	100	4E42	4.54	.31	5.92	4.66	92.0	1.58	2.91	30.95		10.58	33.86	.44
FAGU003	2464	46.7	48.8	2.1	100	4G4	4.59	.08	10.70	7.22	142.0	.89	3.79	18.25		17.92	22.04	.40
FAGU003	2465	48.8	49.7	.9	78	4C@8	5.00	.13	2.54	2.31	40.0	.75	3.57	15.22		4.85	18.79	.48
FAGU003	2466	49.7	51.1	1.4	100	4L2	3.45	.10	1.11	1.08	11.0	.41	5.56	7.27		2.19	12.83	.49
FAGU003	2467	51.1	52.8	1.7	100	4C8	4.46	.25	1.93	1.85	26.0	.82	10.23	16.73		3.78	26.96	.49
FAGU003	2470	72.2	73.9	1.7	100	4CG	3.96	.26	4.87	3.57	76.0	.75	8.10	18.60		8.44	26.70	.42
FAGA021	2471	171.4	172.1	.7	100	4A10	2.98	.03	1.45	3.33	22.0	.27	3.77	2.44		4.78	6.21	.70
FAGA021	2473	198.7	200.3	1.6	94	4A1	3.17	.10	.29	.75	13.0	.34	.85	14.50		1.04	15.35	.72
FAGA021	2474	200.3	201.3	1.0	100	4A1		.07	.67	.87	10.0	.34				1.54		.56
FAGA021	2475	201.3	203.2	1.9	68	4L0		.02	.21	.28	1.0	.17				.49		.57
FAGAC21	2476	210.1	212.4	2.3	91	4A1		.06	.93	1.71	12.0	.34				2.64		.65
FAGA021	2477	212.4	214.5	2.1	100	4A1		.12	.18	.52	14.0	.34				.70		.74
FAGA021	2478	214.5	216.9	2.4	92	4A1		.07	.29	.30	6.0	.17				.59		.51
FAGAC21	2479	216.9	218.6	1.7	88	4A1		.04	.83	1.33	12.0	.34				2.16		.62
FAGAC21	2480	218.6	221.0	2.4	100	4A1	2.96	.05	1.56	2.39	22.0	.55	.79	3.88		3.95	4.67	.61
FAGA021	2481	221.0	222.9	1.9	100	4A1	3.04	.07	.28	.47	10.0	.34	.73	10.40		.75	11.13	.63
FAGAC21	2482	222.9	223.9	1.0	90	4A1	3.56	.17	.39	.86	15.0	.55	.87	18.20		1.25	19.07	.69
FAGA021	2483	223.9	225.2	1.3	100	4A1	3.45	.17	.85	1.62	20.0	.82	1.06	19.00		2.47	20.06	.66
FAGA021	2484	225.2	226.6	1.4	93	4A1	3.42	.12	1.12	.89	22.0	.89	.95	18.30		2.01	19.25	.44
FAGA021	2485	226.6	228.0	1.4	100	4A1		.19	.13	.48	10.0	.34				.61		.79
FAGA021	2486	228.0	229.5	1.5	93	4A1		.15	.05	.04	7.0	.34				.09		.44

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAO	PB+ZN	PC+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGA021	2487	229.5	231.0	1.5	80	4A1		.16	.08	.10	11.0	.34				.18		.56
FAGA021	2488	231.0	232.6	1.6	75	4A1		.15	.12	.37	12.0	.17				.49		.76
FAGA021	2489	232.6	234.1	1.5	87	4A1		.09	.72	.95	18.0	.34				1.67		.57
FAGA021	2490	234.1	236.2	2.1	71	4A1		.11	.80	1.20	15.0	.34				2.00		.60
FAGA021	2491	236.2	237.4	1.2	92	4A1		.11	.50	.87	12.0	.34				1.37		.64
FAGA021	2492	237.4	239.0	1.6	94	4A1		.30	.28	.30	10.0	.34				.58		.52
FAGA021	2493	239.0	240.5	1.5	100	4A1		.40	.15	.33	12.0	.34				.48		.69
FAGA021	2494	240.5	242.0	1.5	87	4A1		.13	.08	.21	3.0					.29		.72
FAGA021	2495	242.0	243.5	1.5	87	4A1		.11	.06	.17	2.0					.23		.74
FAGA021	2496	243.5	244.9	1.4	100	4A1	3.15	.31	.10	.39	10.0	.48	1.20	11.84		.49	13.04	.80
FAGA021	2497	244.9	246.4	1.5	100	4A1		.19	.06	.51	6.0					.57		.89
FAGA021	2498	246.4	248.4	2.0	90	4E0	4.50	.33	1.91	2.74	50.0	.82	1.05	36.20		4.65	37.25	.59
FAGA056	2499	96.4	97.2	.8	87	4D42	2.94	.19	11.90	19.80	147.0	1.85	2.88	14.76		31.70	17.64	.62
FAGAC56	2500	97.2	98.8	1.6	94	4A4	3.36	.04	3.26	6.94	42.0	.89	1.98	7.86		10.20	9.84	.68
FAGA074	5001	93.9	95.4	1.5	100	4L0	2.90	.25	.25	.22	9.0	.14				.47		.47
FAGA074	5002	95.4	96.8	1.4	100	4CL	3.22	.25	.86	.52	16.0	.14				1.38		.38
FAGA074	5003	96.8	98.2	1.4	100	4E4	3.79	.22	2.13	2.35	32.0	.55				4.48		.52
FAGA074	5004	98.5	100.0	1.5	100	4C3	3.85	.20	2.83	1.02	43.0	1.85				3.85		.26
FAGA074	5005	100.0	101.5	1.5	100	4C3	3.69	.24	.40	.30	17.0	.55				.70		.43
FAGA074	5006	101.5	103.0	1.5	100	4C3	3.40	.33	.14	.22	14.0	.41				.36		.61
FAGAC74	5007	103.0	104.5	1.5	93	4C3	3.59	.40	.66	.34	21.0	1.10				1.00		.34
FAGA074	5008	104.5	106.1	1.6	81	4C3	3.64	.38	.11	.13	8.0	1.44				.24		.54
FAGA074	5009	106.1	107.6	1.5	100	4C3	3.91	.57	.09	.18	11.0	1.58				.27		.67
FAGA074	5010	107.6	109.1	1.5	100	4C3	3.79	.40	.10	.22	11.0	1.10				.32		.69
FAGA074	5011	109.1	110.6	1.5	100	4C3	3.91	.52	.14	.40	11.0	.96				.54		.74
FAGA074	5012	110.6	112.2	1.6	100	4C3	3.53	.25	.10	.40	10.0	.69				.50		.80
FAGA074	5013	112.2	114.3	2.1	100	4LA	3.03	.13	.12	.51	7.0	.21				.63		.81
FAGA074	5014	157.1	158.7	1.6	100	4C3	3.31	.20	.75	.61	15.0	.48				1.36		.45
FAGA074	5015	160.3	161.5	1.2	100	4C8	3.67	.26	2.15	2.37	30.0	.69				4.52		.52
FAGA074	5016	161.5	162.9	1.4	100	4D8	3.97	.22	3.27	3.34	43.0	1.03				6.61		.51
FAGAC74	5017	162.9	164.3	1.4	100	4A3	3.36	.18	.23	.24	7.0	.55				.47		.51
FAGAC74	5018	164.3	165.5	1.2	100	4A3	3.48	.19	.14	.15	14.0	.62				.29		.52
FAGA074	5019	165.5	166.7	1.2	100	4A3	3.36	.17	.17	.12	8.0	.55				.29		.41
FAGA074	5020	166.7	167.9	1.2	100	4A3	3.57	.16	.06	.05	11.0	.62				.11		.45
FAGA074	5021	167.9	169.2	1.3	100	4A3	3.34	.24	.14	.26	13.0	.62				.40		.65
FAGA074	5022	169.2	170.4	1.2	75	4A3	3.31	.24	.18	.36	14.0	.55				.54		.67
FAGA074	5023	170.4	171.3	.9	67	4A3	3.34	.16	.16	.26	11.0	.41				.42		.62
FAGA074	5024	171.3	172.8	1.5	100	4L0	3.04	.09	.10	.16	7.0	.27				.26		.62
FAGA074	5025	172.8	174.1	1.3	100	4L0	3.20	.14	2.08	2.22	27.0	.34				4.30		.52
FAGA074	5026	174.1	175.3	1.2	100	4G4	4.07	.19	4.40	5.83	70.0	1.03				10.23		.57
FAGA074	5027	175.3	176.6	1.3	100	4C3	3.47	.31	.15	.26	6.0	.69				.41		.63
FAGA074	5028	178.3	179.8	1.5	100	4C3	3.41	.28	.20	.57	6.0	.48				.77		.74
FAGA074	5029	179.8	181.3	1.5	100	4C3	3.63	.31	.23	.50	5.0	.48				.73		.68
FAGA074	5030	181.4	183.0	1.6	100	4C3	3.81	.37	.11	.29	8.0	.55				.40		.73
FAGAC74	5031	183.0	184.6	1.6	100	4C3	3.50	.44	.41	.71	12.0	.69				1.12		.63
FAGAC74	5032	185.0	186.9	1.9	100	4C3	3.57	.11	1.43	2.61	21.0	1.17				4.04		.65
FAGA074	5033	187.9	189.4	1.5	100	4A3	3.52	.31	.12	.38	12.0	.48				.50		.76
FAGA074	5034	189.4	191.1	1.7	100	4A3	3.31	.18	.10	.13	9.0	.75				.23		.57
FAGA074	5035	191.1	192.6	1.5	100	4A0	3.23	.15	.31	.16	11.0	.69				.47		.34
FAGAC74	5036	192.6	194.3	1.7	100	4A0	3.24	.18	.17	.25	9.0	.55				.42		.60

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAO	PS+ZN	PC+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGA074	5037	194.3	195.8	1.5	100	4A0	3.24	.12	.40	.14	13.0	.62				.54		.26
FAGA074	5038	195.8	197.5	1.7	100	4A3	3.37	.17	.43	.08	17.0	.75				.51		.16
FAGA074	5039	197.5	199.0	1.5	100	4A3	3.48	.28	.09	.25	12.0	.48				.34		.74
FAGA074	5040	199.0	200.6	1.6	100	4A3	3.41	.22	.09	.22	8.0	.48				.31		.71
FAGA074	5041	200.6	202.1	1.5	100	4A3	3.50	.27	.07	.24	9.0	.55				.31		.77
FAGA074	5042	202.1	203.6	1.5	100	4A3	3.31	.18	.40	.18	12.0	.75				.58		.31
FAGA074	5043	203.6	205.1	1.5	100	4A3	3.44	.21	.21	.19	11.0	.48				.40		.48
FAGA074	5044	205.1	206.7	1.6	69	4A4	3.79	.20	2.69	2.98	40.0	.62				5.67		.53
FAGA074	5045	206.7	208.2	1.5	100	4A3	3.33	.18	.28	.15	11.0	.75				.43		.35
FAGA074	5046	208.2	209.7	1.5	100	4A3	3.32	.24	.27	.23	10.0	.55				.50		.46
FAGA074	5047	209.7	210.9	1.2	100	4A0	3.25	.15	.50	.74	12.0	.34				1.24		.60
FAGA074	5048	210.9	212.0	1.1	100	4A4	4.37	.16	6.63	7.73	100.0	.82				14.36		.54
FAGA074	5049	212.0	213.4	1.4	100	4L5	2.96	.02	.18	.18	5.0	.14				.36		.50
FAGA074	5050	213.4	214.6	1.2	100	4L5	3.24	.20	1.62	1.12	23.0	.34				2.74		.41
FAGA023	5051	86.7	88.5	1.8		4A0	2.98	.05	1.04	1.71	14.0	.34	1.70	6.50		2.75	8.20	.62
FAGA023	5052	88.5	89.3	.8		4C0	3.18	.17	.44	.97	11.0	.27	4.94	7.10		1.41	12.04	.69
FAGA023	5053	89.3	91.1	1.8		4A0	3.02	.06	1.13	2.30	16.0	.48	1.35	7.40		3.43	8.75	.67
FAGA023	5054	91.1	93.0	1.9		4A0	2.94	.10	.70	1.43	15.0	.48	1.84	7.20		2.13	9.04	.67
FAGA023	5055	93.0	94.8	1.8		4A0	2.98	.10	.45	1.08	4.0	.48	1.51	7.10		1.53	8.61	.71
FAGA023	5056	94.8	96.6	1.8		4A0	2.94	.08	.53	1.24	14.0	.41	1.18	6.30		1.77	7.48	.70
FAGA023	5057	96.6	98.1	1.5		4A0	2.97	.07	.52	.88	10.0	.34	.84	7.00		1.40	7.84	.63
FAGA023	5058	98.1	99.7	1.6		4A0	3.04	.07	2.08	1.82	28.0	.48	.97	7.70		3.90	8.67	.47
FAGA023	5059	99.7	100.9	1.2		4A4	3.41	.17	3.06	6.36	50.0	.75	1.66	13.40		9.42	15.06	.68
FAGA023	5060	100.9	102.6	1.7		4E4	4.58	.19	6.04	10.66	94.0	1.71	1.39	26.40		16.70	27.79	.64
FAGA023	5061	102.6	104.4	1.8		4E4	4.67	.26	5.96	11.80	104.0	.55	2.07	24.50		17.76	26.57	.66
FAGA023	5062	104.4	104.9	.5		4L0	4.45	.18	5.44	10.40	102.0	.55	2.55	25.40		15.84	27.95	.66
FAGA023	5063	104.9	105.5	.6		4E4	4.11	.15	5.86	12.97	86.0	1.03	2.69	24.60		18.83	27.29	.69
FAGA023	5064	105.8	108.2	2.4		4G4	4.58	.01	2.64	7.45	51.0	.34	2.45	17.20		10.09	19.65	.74
FAGA023	5065	108.2	108.7	.5		4EL	3.59	.05	2.83	11.71	43.0	.75	8.31	10.90		14.54	19.21	.81
FAGA023	5066	110.9	112.7	1.8		4EGK	4.55	.07	2.72	4.96	47.0	.34	1.26	26.50		7.68	27.76	.65
FAGA023	5067	114.9	116.4	1.5		4A4	4.01	.09	8.06	17.50	153.0	1.23	2.46	12.80		25.56	15.26	.68
FAGA023	5068	116.4	118.0	1.6		4A4	3.74	.07	10.60	18.60	178.0	1.65	3.69	6.20		29.20	9.89	.64
FAGA023	5069	118.0	119.2	1.2		4A4	3.44	.11	8.04	17.60	169.0	1.58	2.42	9.20		25.64	11.62	.69
FAGA023	5070	119.2	119.8	.6		4L0	3.82	.03	7.52	17.70	100.0	.82	3.74	11.20		25.22	14.94	.70
FAGA023	5071	119.8	121.3	1.5		4E4	3.83	.11	9.09	19.91	129.0	1.65	2.17	12.50		29.00	14.67	.69
FAGA023	5072	121.3	122.8	1.5		4E4	4.16	.03	13.20	22.30	158.0	1.13	2.83	14.00		35.50	16.83	.63
FAGA023	5073	122.8	124.7	1.9		4E4	4.25	.10	7.27	12.51	137.0	1.44	2.43	25.10		19.78	27.53	.63
FAGA023	5074	124.7	126.5	1.8		4E4	4.06	.14	5.34	10.71	100.0	1.65	2.74	24.70		16.05	27.44	.67
FAGA023	5075	126.5	128.0	1.5		4A3	3.09	.15	.24	1.30	12.0	.55	2.00	15.40		1.54	17.40	.84
FAGA023	5076	128.0	129.5	1.5		4A3	3.07	.12	.44	1.03	12.0	.48	2.41	16.00		1.47	18.41	.70
FAGA023	5077	129.5	131.1	1.6		4A3	3.45	.14	.21	1.21	14.0	.55	2.01	20.20		1.42	22.21	.85
FAGA023	5078	131.1	132.6	1.5		4A4	3.28	.10	2.95	5.47	38.0	1.03	2.50	14.70		8.42	17.20	.65
FAGA023	5079	132.6	134.3	1.7		4A4	3.12	.06	3.86	6.69	49.0	1.17	2.51	9.60		10.55	12.11	.63
FAGA023	5080	134.3	135.8	1.5		4E4	4.02	.03	7.69	18.50	134.0	1.03	3.59	14.90		26.19	18.49	.71
FAGA023	5081	135.8	137.5	1.7		4E4	4.07	.13	7.47	15.31	119.0	1.71	2.53	18.60		22.78	21.13	.67
FAGA023	5082	137.5	139.3	1.8		4A4	3.30	.11	4.16	5.44	48.0	1.65	2.45	11.40		9.60	13.85	.57
FAGA023	5083	139.3	141.2	1.9		4A3	3.39	.09	2.16	2.46	28.0	.96	1.71	17.10		4.62	18.81	.53
FAGA023	5084	141.2	143.0	1.8		4A3	3.36	.13	.34	.67	10.0	.89	1.85	18.50		1.01	20.35	.66
FAGA023	5085	143.0	144.6	1.6		4A3	2.97	.14	.41	.81	10.0	.55	2.82	18.90		1.22	21.72	.66
FAGA023	5086	144.6	145.5	.9		4E14	3.76	.09	1.78	3.58	28.0	.62	4.27	23.00		5.36	27.27	.67

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	SAO	PB+ZN	PO+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGA023	5087	145.5	147.2	1.7		4A0	3.18	.14	.71	1.92	15.0	.75	1.84	15.50		2.63	17.34	.73
FAGA023	5088	147.2	149.0	1.8		4A0	3.18	.11	.47	.94	14.0	.55	1.55	16.50		1.41	18.05	.67
FAGA023	5089	149.0	150.9	1.9		4A0	2.94	.17	.23	.70	8.0	1.78	2.29	16.80		.93	19.09	.75
FAGA023	5090	150.9	152.7	1.8		4A0	3.16	.14	.20	1.18	8.0	.48				1.38		.86
FAGA023	5091	152.7	154.5	1.8		4A0	3.00	.29	.11	1.79	8.0	.41				1.90		.94
FAGA023	5092	154.5	156.4	1.9		4A0	3.17	.18	.51	1.01	15.0	.48				1.52		.66
FAGA023	5093	156.4	158.7	2.3		4A3	2.22	.40	.42	.35	13.0	.41	4.17	18.20		.77	22.37	.45
FAGA023	5094	158.7	160.3	1.6		4C3	3.59	.53	.18	.37	14.0	.48	4.49	21.30		.55	25.79	.67
FAGA023	5095	160.3	161.8	1.5		4C3	3.59	.35	1.23	2.78	30.0	.89	2.46	18.90		4.01	21.36	.69
FAGA023	5096	161.8	163.4	1.6		4C3	4.31	.40	1.72	1.51	38.0	1.51	2.35	35.30		3.23	37.65	.47
FAGA023	5097	163.4	165.4	2.0		4E0	4.12	.34	1.24	1.23	26.0	1.51	2.35	29.90		2.47	32.25	.50
FAGA023	5098	165.4	167.4	2.0		4E1	3.77	.29	.61	.37	21.0	.96	4.30	25.50		.98	29.80	.38
FAGA023	5099	167.4	168.9	1.5		4C3	3.61	.44	.10	.88	8.0	.75	5.40	20.20		.98	25.60	.90
FAGA023	5100	168.9	170.1	1.2		4C3	3.37	.30	.06	.60	8.0	1.58				.66		.91
FAGA074	5101	223.3	224.8	1.5	100	4C7	3.50	.28	1.57	1.36	22.0	.07				2.93		.46
FAGA074	5102	290.5	292.0	1.5	60	4C3	3.43	.02	.11	.07	5.0	.07				.18		.39
FAGA074	5103	292.0	293.4	1.4	64	4C3	3.48	.01	.04	.02	4.0	.07				.06		.33
FAGA052	5104	157.7	159.2	1.5		4A4	3.14	.04	3.17	5.70	50.0	.48	8.36	2.94		8.87	11.30	.64
FAGA052	5105	159.2	160.5	1.3		4A4	3.19	.03	2.41	4.84	47.0	.41	11.30	2.47		7.25	13.77	.67
FAGA052	5106	175.6	176.8	1.2		4E4	4.52	.19	4.80	4.92	57.0	1.17	3.96	27.30		9.72	31.26	.51
FAGA052	5107	176.8	177.5	.7		4G4	4.70	.06	4.88	7.85	69.0	.69	.71	16.10		12.73	16.81	.62
FAGA052	5108	177.5	179.6	2.1		4E0	3.95	.25	1.56	2.26	34.0	1.51	5.93	23.70		3.82	29.63	.59
FAGA052	5109	179.6	181.7	2.1		4E84	3.93	.14	2.51	3.99	44.0	1.03	8.84	19.60		6.50	28.44	.61
FAGA052	5110	181.7	182.9	1.2		4E4	3.89	.09	3.32	5.46	49.0	.89	11.07	17.10		8.78	28.17	.62
FAGA052	5111	182.9	184.1	1.2		4E4	4.30	.11	4.87	5.38	68.0	1.30	7.50	23.80		10.25	31.30	.52
FAGA052	5112	184.1	185.9	1.8		4C83	3.52	.33	1.58	2.93	31.0	.62	7.95	15.40		4.51	23.35	.65
FAGA052	5113	185.9	187.9	2.0		4C83	3.63	.34	.67	1.36	14.0	.41	12.14	13.90		2.03	26.04	.67
FAGA052	5114	187.9	189.6	1.7		4C3	3.58	.21	1.27	2.22	18.0	.55	7.95	16.70		3.49	24.65	.64
FAGA052	5115	189.6	191.4	1.8		4C3	3.31	.29	.38	.43	9.0	.48	7.59	11.90		.81	19.49	.53
FAGA052	5116	191.4	193.2	1.8		4C0	3.18	.75	.19	.33	10.0	.27				.52		.63
FAGA052	5117	193.2	195.1	1.9		4C0	3.29	.23	.39	.62	10.0	.21				1.01		.61
FAGA052	5118	195.1	196.9	1.8		4C3	3.88	.15	.35	.37	7.0	.27				.72		.51
FAGA052	5119	196.9	198.7	1.8		4C0	3.21	.30	.62	.19	8.0	.34				.81		.23
FAGA052	5120	198.7	200.6	1.9		4C0	3.24	.30	.24	.20	5.0	1.17				.44		.45
FAGA052	5121	200.6	202.4	1.8		4C0	3.19	.31	.26	.43	8.0	.21				.69		.62
FAGA052	5122	202.4	203.6	1.2		4C0	3.06	.16	.24	.20	7.0	.21				.44		.45
FAGA052	5123	203.6	205.0	1.4		4C0	2.91	.05	.43	.20	7.0	.21				.63		.32
FAGU183	5128	.0	1.6	1.6		4E4	4.55	.20	5.23	11.40	84.0	.75	3.23	25.90		16.63	29.13	.69
FAGU183	5129	1.6	3.0	1.4		4A0	3.07	.11	2.57	1.83	43.0	.82	1.54	13.30		4.40	14.84	.42
FAGU183	5130	3.0	6.0	3.0		4AC3	3.68	.15	1.75	3.18	34.0	1.23	1.71	21.00		4.93	22.71	.65
FAGU183	5131	6.0	7.5	1.5		4A34	3.42	.10	2.86	3.48	41.0	1.10	1.65	15.40		6.34	17.05	.55
FAGU183	5132	7.5	9.7	2.2		4A34	3.42	.08	3.90	6.69	52.0	1.23	2.63	12.60		10.59	15.23	.63
FAGU183	5133	9.7	11.2	1.5		4E4	4.52	.22	6.09	12.00	93.0	2.33	4.21	25.40		18.09	29.61	.66
FAGU183	5134	11.2	12.7	1.5		4E4	4.45	.18	8.00	15.10	142.0	1.65	2.87	22.40		23.10	25.27	.65
FAGU183	5135	12.7	14.2	1.5		4E4	4.30	.06	7.32	13.10	130.0	1.37	2.45	21.30		20.42	23.75	.64
FAGU183	5136	14.2	15.7	1.5		4E4	3.71	.23	3.90	7.63	78.0	1.51	2.40	17.60		11.53	20.00	.66
FAGU183	5137	15.7	17.2	1.5		4E4	4.09	.20	4.95	9.50	75.0	1.51	3.00	22.10		14.45	25.10	.66
FAGU183	5138	17.2	18.3	1.1		4E4	4.35	.20	4.57	13.20	91.0	1.65	5.96	21.50		17.77	27.46	.74
FAGU183	5139	18.3	20.3	2.0		4D4	3.61	.03	7.13	20.60	177.0	1.17	4.84	6.00		27.73	10.84	.74
FAGU183	5140	20.3	21.9	1.6		4D4	3.54	.05	8.08	18.20	143.0	1.23	3.89	5.70		26.28	9.59	.69

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAO	PB+ZN	PO+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGA164	5141	83.2	84.9	1.7	88	5A0	2.88	.01	.71	2.03	17.0	.07	1.50	2.00		2.74	3.50	.74
FAGA164	5142	84.9	86.4	1.5	47	4A4	2.85	.01	1.57	3.63	35.0	.07	1.04	1.15		5.20	2.19	.70
FAGA164	5143	86.4	87.9	1.5	53	4A4	2.89	.02	1.30	4.35	23.0	.07	4.13	17.80		5.65	21.93	.77
FAGA164	5144	87.9	89.4	1.5	27	4A0	2.83	.01	.67	2.39	11.0	.07	1.37	21.20		3.06	22.57	.78
FAGA023	5151	170.1	171.6	1.5		4A0	2.95	.15	.03	.50	3.0	.48	2.78	9.70		.53	12.48	.94
FAGAG23	5152	171.6	173.4	1.8		4A3	3.34	.19	.16	.42	7.0	1.03	3.06	17.80		.58	20.86	.72
FAGAG23	5153	173.4	175.0	1.6		4E0	4.62	.32	1.39	2.09	31.0	1.85	1.68	37.30		3.48	38.98	.60
FAGA023	5154	175.0	176.2	1.2		4E0	3.76	.09	1.20	1.53	18.0	1.10	4.75	27.30		2.73	32.05	.56
FAGAG23	5155	235.6	237.4	1.8		4E14	3.34	.07	4.59	7.11	64.0	.21	5.90	8.30		11.70	14.20	.61
FAGAG23	5156	237.4	239.4	2.0		4LC	2.80	.04	.11	.22	3.0	.07	28.10	4.30		.33	32.40	.67
FAGA023	5157	239.4	240.9	1.5		4E4	4.45	.27	3.24	4.08	55.0	1.58	4.87	26.80		7.32	31.67	.56
FAGA023	5158	240.9	242.4	1.5		4E0	4.49	.40	1.74	1.50	33.0	1.37	7.09	29.80		3.24	36.89	.46
FAGA023	5159	242.4	243.9	1.5		4E0	4.50	.42	2.76	1.75	38.0	1.23	9.04	29.20		4.51	38.24	.39
FAGA023	5160	243.9	245.2	1.3		4E4	4.60	.21	2.36	3.18	42.0	1.03	6.55	31.50		5.54	38.05	.57
FAGA023	5161	262.9	264.0	1.1		4A0	3.07	.17	.88	1.17	17.0	.41	4.70	10.60		2.05	15.30	.57
FAGA023	5162	264.0	265.2	1.2		4H3	5.19	.27	.60	.35	19.0	.27	13.50	18.80		.95	32.30	.37
FAGA023	5163	265.2	267.0	1.8		4A0	3.05	.22	.60	.69	14.0	.34	2.68	10.30		1.29	12.98	.53
FAGA023	5164	275.3	277.2	1.9		4A0	3.37	.22	1.95	1.78	32.0	.82				3.73		.48
FAGA023	5165	278.5	280.4	1.9		4A0	3.28	.16	.85	1.05	20.0	.27				1.90		.55
FAGA147	5166	43.7	46.1	2.4		4A0	2.88	.03	1.22	3.78	32.0	.41	1.60	3.88		5.00	5.48	.76
FAGA147	5167	47.4	48.0	.6		4A0	2.91	.06	1.15	2.62	20.0	.34	1.31	4.94		3.77	6.25	.69
FAGA147	5168	48.0	49.4	1.4		4L2	2.91	.05	.81	2.05	15.0	.27	2.24	3.96		2.86	6.20	.72
FAGA147	5169	49.4	51.0	1.6		4A0	2.95	.12	.74	1.45	12.0	.48	1.45	6.50		2.19	7.95	.66
FAGA147	5170	51.0	52.7	1.7		4A0	3.00	.09	1.40	3.39	21.0	.41	2.13	7.80		4.79	9.93	.71
FAGA147	5171	77.6	78.6	1.0		5B19	2.92	.06	.50	.80	8.0	.48				1.30		.62
FAGA147	5172	82.0	85.2	3.2		5B19	2.92	.15	.64	1.29	15.0	.27				1.93		.67
FAGA147	5173	85.2	88.4	3.2		4L42	2.85	.04	.25	.76	3.0	.07				1.01		.75
FAGA147	5174	88.4	90.0	1.6		5B19	2.88	.05	.61	1.36	9.0	.27				1.97		.69
FAGA147	5175	90.0	92.0	2.0		5B19	2.84	.07	.30	.58	7.0	.21				.88		.66
FAGA147	5176	92.0	94.0	2.0		5B19	2.58	.03	.55	1.41	7.0	.14				1.96		.72
FAGA147	5177	94.0	97.0	3.0		5B19	2.90	.03	.58	1.49	7.0	.21				2.07		.72
FAGA147	5178	97.0	99.0	2.0		4A3	3.44	.15	.61	1.07	25.0	.69	2.23	18.60		1.68	20.83	.64
FAGA147	5179	99.0	101.0	2.0		4A0	3.25	.10	.49	2.38	17.0	.62	3.54	13.30		2.87	16.84	.83
FAGA147	5180	101.0	103.0	2.0		4A4	3.26	.10	2.99	5.07	52.0	.75	2.81	11.20		8.06	14.01	.63
FAGA147	5181	103.0	105.0	2.0		4A0	3.14	.10	.49	1.29	15.0	.48	1.68	12.80		1.78	14.48	.72
FAGA147	5182	105.0	106.8	1.8		4A0	3.03	.11	.75	1.38	20.0	.48				2.13		.65
FAGA147	5183	146.9	148.4	1.5		4C0	3.03	.06	.50	.92	9.0	.41				1.42		.65
FAGA147	5184	148.4	150.0	1.6		4A0	2.83	.08	.32	.50	6.0	.14				.82		.61
FAGA147	5185	150.0	152.0	2.0		4A0	2.90	.09	.27	.61	8.0	.21				.88		.69
FAGA147	5186	152.0	154.5	2.5		4A0	2.91	.07	.71	1.29	15.0	.21				2.00		.65
FAGA147	5187	154.5	156.1	1.6		4L1	2.93	.07	.10	.21	2.0	.14				.31		.68
FAGA147	5188	156.1	157.6	1.5		4A0	3.00	.20	.33	.67	9.0	.27				1.00		.67
FAGA147	5189	160.7	163.4	2.7		4AC	2.92	.20	.04	.29	6.0	.27				.33		.88
FAGA147	5190	163.4	165.4	2.0		4C3	3.26	.17	.04	.27	7.0	.21				.31		.87
FAGA147	5191	165.4	166.7	1.3		4A0	3.01	.24	.04	.60	9.0	.41				.64		.94
FAGA147	5192	166.7	167.5	.8		4C0	3.11	.15	.10	.63	7.0	.27	2.98	12.70		.73	15.68	.86
FAGA147	5193	167.5	168.5	1.0		4CA3	3.61	.22	.78	2.25	21.0	1.10	2.65	21.90		3.03	24.55	.74
FAGA147	5194	168.5	170.6	2.1		4E14	4.41	.16	3.08	4.65	43.0	1.30	1.30	30.90		7.73	32.20	.60
FAGA147	5195	171.8	172.8	1.0		4D43	4.01	.10	4.73	8.22	61.0	1.30	1.35	23.10		12.95	24.45	.63
FAGA147	5196	172.8	174.4	1.6		4A0	3.08	.09	1.40	3.29	33.0	.69	1.13	10.20		4.69	11.33	.70

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAO	PB+ZN	PO+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGA147	5197	174.4	175.2	.8		4E1	3.43	.03	.65	1.23	21.0	.89	2.86	32.10		1.88	34.96	.65
FAGA147	5198	175.2	175.9	.7		4AD	3.43	.06	3.08	4.94	51.0	.48	1.79	14.20		8.02	15.99	.62
FAGA145	5199	41.8	43.3	1.5	100	4LC	3.11	.09	.81	.94	13.0	.41				1.75		.54
FAGA145	5200	48.0	50.3	2.3	83	4K4	4.52	.12	11.40	12.80	148.0	.89	3.89	21.90		24.20	25.79	.53
FAGAC17	5201	210.0	213.4	3.4		4H0	3.86	.50	1.86	1.51	28.0	.21	28.75	8.00		3.37	36.75	.45
FAGA017	5202	216.7	221.6	4.9		4H0	3.63	.28	1.80	1.78	27.0	.48	16.36	10.40		3.58	26.76	.50
FAGA017	5203	227.1	229.5	2.4		4C37	3.75	.21	1.58	1.35	27.0	.41	16.22	12.90		2.93	29.12	.46
FAGA017	5204	239.9	243.4	3.5		4K6	3.29	.09	1.14	.94	17.0	.34	10.32	7.60		2.08	17.92	.45
FAGA017	5205	243.4	246.3	2.9		4K6	4.81	.16	1.26	2.07	21.0	.55	6.03	11.70		3.33	17.73	.62
FAGA017	5206	246.3	249.5	3.2		4K6	3.32	.15	.99	1.17	16.0	.55	2.97	16.50		2.16	19.47	.54
FAGA017	5207	249.5	252.5	3.0		4K6	3.74	.24	1.96	1.75	32.0	1.03	5.86	19.50		3.71	25.36	.47
FAGA017	5208	252.5	253.9	1.4		4K6	3.64	.25	1.42	1.05	22.0	.82	7.98	20.80		2.47	28.78	.43
FAGAC17	5209	259.4	261.5	2.1		4K0	3.86	.47	1.46	.79	26.0	1.03	14.20	18.40		2.25	32.60	.35
FAGA013	5210	40.8	44.0	3.2	100	4K7	3.70	.20	1.32	.87	34.0	.27	6.00	20.70		2.19	26.70	.40
FAGA013	5211	123.1	124.9	1.8	100	4E4	3.70	.13	3.06	5.09	68.0	.55	2.59	18.30		8.15	20.89	.62
FAGAC13	5212	130.1	133.2	3.1	100	4A0	3.01	.07	.78	1.65	12.0	.34	1.99	4.50		2.43	6.49	.68
FAGA013	5213	133.2	136.6	3.4	100	4A0	2.99	.11	.81	1.54	14.0	.34	2.07	4.97		2.35	7.04	.66
FAGA145	5214	78.3	80.0	1.7	88	4CAD	3.57	.14	1.39	2.85	26.0	.96	2.36	19.60		4.24	21.96	.67
FAGA145	5215	80.0	83.1	3.1	77	4K4	4.59	.29	3.28	3.59	55.0	1.17	2.97	33.70		6.87	36.67	.52
FAGA106	5216	46.9	49.2	2.3	100	4E4	4.14	.06	10.79	8.03	153.0	1.03	2.16	20.10		18.82	22.26	.43
FAGA106	5217	49.2	50.5	1.3	100	4LK	3.03	.03	1.36	3.52	14.0	.14	4.39	3.46		4.88	7.85	.72
FAGA106	5218	90.3	91.4	1.1	82	4E4	4.16	.09	11.60	8.03	139.0	1.37				19.63		.41
FAGA106	5219	151.3	154.2	2.9	100	4AG	4.40	.05	5.48	9.05	97.0	.48	1.19	10.70		14.53	11.89	.62
FAGA106	5220	154.2	154.8	.6	100	4E4	4.52	.11	5.32	6.77	87.0	.89	1.87	27.10		12.09	28.97	.56
FAGA106	5221	154.8	157.0	2.2	100	4D4	3.92	.06	6.82	9.21	96.0	.75	4.06	18.20		16.03	22.26	.57
FAGA106	5222	157.0	159.8	2.8	100	4C3	3.52	.10	1.93	2.38	37.0	.75	3.84	18.20		4.31	22.04	.55
FAGA106	5223	159.8	162.0	2.2	91	4A4	3.04	.06	3.82	5.53	54.0	.75	2.14	7.00		9.35	9.14	.59
FAGA106	5224	162.0	163.9	1.9	84	4A0	2.92	.03	1.26	1.88	24.0	.41	2.69	3.09		3.14	5.78	.60
FAGA106	5225	168.7	172.0	3.3	100	4A0	3.23	.19	.16	.49	8.0	.27				.65		.75
FAGA106	5226	172.0	175.0	3.0	87	4A3	3.37	.23	.13	.27	7.0	.34				.40		.68
FAGA106	5227	175.0	178.0	3.0	100	4A3	3.37	.24	.26	.36	10.0	.21				.62		.58
FAGA106	5228	178.0	181.3	3.3	88	4L2	3.02	.18	.22	.35	6.0	.07				.57		.61
FAGU181	5229	.0	1.5	1.5	80	4E4	4.52	.16	6.37	13.55	134.0	.96	4.52	23.20		19.92	27.72	.68
FAGU181	5230	1.5	3.0	1.5	100	4E4	4.13	.15	9.20	15.21	149.0	.69	3.81	20.00		24.41	23.81	.62
FAGU181	5231	3.0	4.5	1.5	100	4E4	4.83	.25	7.33	12.03	91.0	1.03	2.57	26.40		19.36	28.97	.62
FAGU181	5232	4.5	6.0	1.5	100	4E4	4.84	.16	4.01	9.15	79.0	.89	3.51	33.30		13.16	36.81	.70
FAGU181	5233	6.0	7.4	1.4	100	4E4	4.38	.24	5.95	12.82	94.0	1.78	3.34	22.60		18.77	25.94	.68
FAGU181	5234	7.4	8.0	.6	100	4G4	4.76	.20	4.86	10.01	113.0	1.65	1.34	15.70		14.87	17.04	.67
FAGU181	5235	8.0	10.0	2.0	100	4D4	3.99	.10	9.80	21.30	167.0	1.30	3.26	11.20		31.10	14.46	.68
FAGU181	5236	10.0	11.8	1.8	100	4D4	3.85	.06	12.60	23.70	199.0	1.51	3.38	7.20		36.30	10.58	.65
FAGU181	5237	49.8	51.3	1.5	100	4G4	4.42	.12	4.68	9.05	105.0	.89	1.69	20.40		13.73	22.09	.66
FAGU181	5238	51.3	52.8	1.5	93	4G4	4.62	.14	6.47	11.90	106.0	1.23	1.45	13.20		18.37	14.65	.65
FAGU181	5239	52.8	54.3	1.5	100	4G4	4.69	.12	5.19	9.73	94.0	1.10	1.49	15.00		14.92	16.49	.65
FAGU181	5240	54.3	55.8	1.5	100	4G4	4.32	.11	4.99	9.07	106.0	.55	1.38	13.60		14.06	14.98	.65
FAGU181	5241	55.8	57.3	1.5	100	4G0	3.44	.07	2.20	5.21	45.0	.41	2.14	8.70		7.41	10.84	.70
FAGU181	5242	57.3	58.8	1.5	100	4G4	4.67	.20	5.78	8.07	118.0	1.30	1.15	21.70		13.85	22.85	.58
FAGU181	5243	58.8	60.4	1.6	100	4G4	4.61	.26	7.32	9.65	166.0	1.65	1.26	24.10		16.97	25.36	.57
FAGA134	5244	67.9	69.2	1.3	100	4AH4	3.34	.07	5.06	5.54	76.0	.55	5.18	7.80		10.60	12.98	.52
FAGA134	5245	72.7	75.0	2.3	100	4K64	3.89	.06	11.60	8.71	161.0	.55	2.22	12.10		20.31	14.32	.43
FAGA134	5246	75.0	78.0	3.0	100	4K64	4.33	.07	16.80	11.10	241.0	.96	2.34	14.80		27.90	17.14	.40

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAO	PB+ZN	PO+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGA134	5247	84.6	86.0	1.4	100	4G4#	4.04	.03	6.76	11.30	104.0	.69	1.70	17.20		18.06	18.90	.63
FAGA134	5248	86.0	87.5	1.5	100	4A4	3.08	.04	3.26	6.53	49.0	.69	2.13	5.70		9.79	7.83	.67
FAGA134	5249	94.0	97.0	3.0	100	4A0	2.83	.04	1.20	2.03	18.0	.55	2.02	3.45		3.23	5.47	.63
FAGA134	5250	97.0	99.5	2.5	100	4A4	3.05	.04	3.04	6.85	49.0	.75	1.86	6.70		9.89	8.56	.69
FAGA134	5251	99.5	102.5	3.0	67	4G4#	3.51	.03	3.77	7.82	55.0	.41	1.70	11.30		11.59	13.00	.67
FAGA134	5252	105.3	107.7	2.4	100	4D0	3.04	.05	3.78	6.08	61.0	.27	2.51	7.00		9.86	9.51	.62
FAGA134	5253	148.9	151.0	2.1	100	4A0	3.00	.04	1.30	1.56	21.0	.62	2.29	8.00		2.86	10.29	.55
FAGA134	5254	151.0	153.8	2.8	100	4A0	3.05	.16	.76	1.41	16.0	.48	3.61	4.34		2.17	7.95	.65
FAGA134	5255	153.8	154.7	.9	100	4G4	4.10	.09	5.17	10.26	87.0	.55	2.78	17.80		15.43	20.58	.66
FAGA134	5256	157.2	159.0	1.8	100	4G34	4.35	.21	6.93	5.43	95.0	.82	5.42	22.30		12.36	27.72	.44
FAGA134	5257	159.0	160.5	1.5	100	4G34	4.51	.06	6.33	7.55	97.0	.41	2.28	15.00		13.88	17.28	.54
FAGA134	5258	160.5	162.0	1.5	100	4G34	4.31	.02	6.54	7.77	72.0	.14	1.68	11.60		14.31	13.28	.54
FAGA134	5259	162.0	163.2	1.2	100	4G3	3.93	.06	3.47	5.93	50.0	.27	2.26	12.90		9.40	15.16	.63
FAGA134	5261	163.7	165.2	1.5	100	4D83	3.97	.19	4.46	3.54	61.0	1.51	8.35	20.40		8.00	28.75	.44
FAGA134	5262	165.2	166.7	1.5	100	4D83	3.87	.14	3.25	1.87	45.0	1.23	4.75	22.50		5.12	27.25	.37
FAGA134	5263	166.7	168.2	1.5	100	4C83	3.81	.35	.63	.20	17.0	1.51	1.70	27.50		.83	29.20	.24
FAGA134	5264	168.2	171.2	3.0	100	4C83	3.72	.36	.17	.17	10.0	.62	3.83	23.80		.34	27.63	.50
FAGA134	5265	171.2	174.2	3.0	100	4C83	3.55	.52	.11	.10	8.0	1.10	6.06	19.90		.21	25.96	.48
FAGA134	5266	174.2	176.2	2.0	100	4C83	3.63	.24	1.55	1.40	25.0	.89	5.84	21.60		2.95	27.44	.47
FAGA134	5267	176.2	178.2	2.0	100	4D48	3.42	.12	4.23	6.01	55.0	.62	6.75	10.00		10.24	16.75	.59
FAGA134	5268	178.2	181.2	3.0	100	4C83	3.67	.13	1.67	1.00	22.0	.34	11.16	18.00		2.67	29.16	.37
FAGA134	5269	181.2	183.2	2.0	100	4H18	3.54	.18	.29	.60	10.0	.41	8.53	17.80		.89	26.33	.67
FAGA134	5270	183.2	185.2	2.0	100	4H18	3.38	.34	.36	.54	12.0	.89				.90		.60
FAGA134	5271	185.2	187.2	2.0	100	4H18	3.32	.26	.37	.57	10.0	.21				.94		.61
FAGA134	5272	187.2	189.7	2.5	100	4H18	3.43	.27	.36	.58	11.0	.62				.94		.62
FAGA142	5301	50.5	51.6	1.1		4CG	3.93	.13	5.98	5.79	72.0	.48	4.99	14.60		11.77	19.59	.49
FAGA142	5302	51.6	53.6	2.0		4EK4	4.57	.07	3.76	2.17	51.0	1.03	1.75	32.40		5.93	34.15	.37
FAGA142	5303	53.6	55.8	2.2		4E0	4.44	.15	2.77	2.24	43.0	1.17	2.35	32.00		5.01	34.35	.45
FAGA142	5304	55.8	57.4	1.6		4KE4	4.46	.17	5.46	2.51	68.0	1.65	5.59	27.50		7.97	33.09	.31
FAGA142	5305	57.4	58.7	1.3		4EG4	4.57	.16	6.90	7.35	85.0	.82	2.56	21.30		14.25	23.86	.52
FAGA142	5306	58.7	60.6	1.9		4E4	4.76	.08	3.01	2.71	49.0	.41	1.41	34.00		5.72	35.41	.47
FAGA142	5307	89.9	90.7	.8		4A4	3.22	.09	2.21	4.82	38.0	1.58	1.92	9.20		7.03	11.12	.69
FAGA142	5308	90.7	92.7	2.0		4E4	4.57	.26	2.84	4.12	47.0	.62	3.71	30.30		6.96	34.01	.59
FAGA142	5309	92.7	93.7	1.0		4E4	4.62	.50	5.71	12.27	99.0	.75	4.81	24.30		17.98	29.11	.68
FAGA142	5310	93.7	95.1	1.4		4E4	4.67	.15	6.45	12.75	95.0	.62	3.76	25.80		19.20	29.56	.66
FAGA142	5311	95.1	98.6	3.5		4A0	2.79	.02	.41	1.65	6.0	.75	3.84	4.73		2.06	8.57	.80
FAGA142	5312	98.6	100.6	2.0		4E4	4.81	.21	5.15	7.55	106.0	.69	2.31	29.90		12.70	32.21	.59
FAGA142	5313	100.6	102.1	1.5		4E4	4.79	.24	4.52	8.47	93.0	.82	2.35	30.60		12.99	32.95	.65
FAGA142	5314	102.1	103.3	1.2		4E4	4.37	.13	3.95	9.08	70.0	.55	4.71	26.90		13.03	31.61	.70
FAGA142	5315	154.9	156.4	1.5		4D43	3.80	.25	6.34	4.25	128.0	.48	3.16	19.40		10.59	22.56	.40
FAGA142	5316	156.4	157.2	.8		4D3	3.86	.28	2.46	3.27	41.0	.27	2.33	25.10		5.73	27.43	.57
FAGA142	5317	157.2	159.2	2.0		4A43	3.50	.10	4.71	8.04	69.0	.69	2.83	15.30		12.75	18.13	.63
FAGA142	5318	159.2	161.5	2.3		4A43	3.56	.11	4.35	7.28	61.0	1.03	2.93	17.70		11.63	20.63	.63
FAGA142	5319	161.5	163.5	2.0		4CA3	3.36	.21	.42	3.98	12.0	.96	4.18	15.90		4.40	20.08	.90
FAGA142	5320	163.5	165.0	1.5		4CA3	3.21	.79	.45	2.73	22.0	.27	5.02	19.90		3.18	24.92	.86
FAGA142	5321	165.0	166.1	1.1		4CA3	3.83	.52	4.17	3.81	69.0	1.37	5.56	22.10		7.98	27.66	.48
FAGA142	5322	198.7	200.4	1.7		4EL	3.65	.26	2.06	2.56	25.0	1.65				4.62		.55
FAGA142	5323	242.8	243.5	.7		4E84	4.26	.18	3.60	3.67	56.0	.89	8.79	24.40		7.27	33.19	.50
FAGA142	5324	243.5	244.3	.8		4L0	2.93	.19	.78	.60	12.0	.34	4.17	3.93		1.38	8.10	.43

DDH	SAMPLE	----DEPTHS----		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAG	PB+ZN	PO+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGA142	5325	244.3	245.1	.8		4E84	4.35	.26	5.23	4.32	69.0	.55	12.89	21.00		9.55	33.89	.45
FAGA142	5326	245.1	245.7	.6		4D3	3.32	.15	3.40	3.11	39.0	1.23	4.63	16.10		6.51	20.73	.48
FAGA142	5327	245.7	247.7	2.0		4E84	3.99	.19	4.38	3.47	56.0	2.06	10.84	21.60		7.85	32.44	.44
FAGA142	5328	247.7	249.2	1.5		4E84	3.78	.18	3.98	3.68	49.0	1.51	9.61	17.50		7.66	27.11	.48
FAGA142	5329	249.2	250.2	1.0		4E84	3.84	.21	4.80	4.29	59.0	.07	10.94	17.80		9.09	28.74	.47
FAGA142	5330	250.2	252.4	2.2		4EL	3.74	.17	2.70	2.57	40.0	.89	10.22	20.70		5.27	30.92	.49
FAGA142	5331	252.4	253.0	.6		4KL	3.97	.08	4.76	3.83	82.0	1.03	10.22	22.50		8.59	32.72	.45
FAGU035	5332	94.5	96.0	1.5	100	4A0	3.11	.09	.43	.67	15.0	.34				1.10		.61
FAGU035	5333	96.0	97.5	1.5	93	4A0	3.28	.12	.34	.97	17.0	.48				1.31		.74
FAGU035	5334	97.5	98.2	.7	100	4A0	3.19	.11	.27	.92	15.0	.48				1.19		.77
FAGU035	5335	100.7	102.1	1.4	100	4A0	3.28	.20	.48	.90	24.0	.48				1.38		.65
FAGU035	5336	102.1	103.6	1.5	100	4A0	3.43	.21	.26	1.26	26.0	.62				1.52		.83
FAGU035	5337	103.6	105.2	1.6	94	4A0	3.28	.14	.12	1.64	8.0	.55				1.76		.93
FAGU035	5338	105.2	106.7	1.5	100	4A0	3.33	.18	.24	1.03	11.0	.34				1.27		.81
FAGU035	5339	108.2	109.7	1.5	100	4A0	3.18	.39	.08	.43	7.0	.14				.51		.84
FAGU035	5340	109.7	110.6	.9	89	4A0	2.93	.16	.02	.33	4.0	.07				.35		.94
FAGA066	5341	107.8	109.7	1.9	47	4AE	2.83	.06	.27	.48	8.0	.41				.75		.64
FAGA066	5342	109.7	112.8	3.1	48	4A0	2.98	.09	.16	.28	7.0	.34				.44		.64
FAGA066	5343	112.8	115.8	3.0	80	4A0	3.01	.10	.33	.71	14.0	.34				1.04		.68
FAGA066	5344	115.8	118.9	3.1	29	4A0	3.21	.18	.91	.41	20.0	.62				1.32		.31
FAGA066	5345	118.9	121.9	3.0	80	4A0	3.35	.15	.37	.44	12.0	.82				.81		.54
FAGA066	5346	121.9	125.0	3.1	97	4A0	3.13	.15	.13	.28	8.0	.55				.41		.68
FAGA066	5347	125.0	128.0	3.0	100	4A0	3.17	.29	.08	.77	14.0	.55				.85		.91
FAGA066	5348	128.0	131.0	3.0	100	4A0	3.30	.44	.13	.53	17.0	.55				.66		.80
FAGA066	5349	131.0	134.1	3.1	100	4A0	2.93	.28	.15	.59	14.0	.34				.74		.80
FAGA066	5350	134.1	137.2	3.1	97	4AE	2.92	.16	.15	.84	9.0	.41				.99		.85
FAGA066	5351	137.2	138.7	1.5	100	4A0	2.93	.24	.05	1.01	8.0	.34				1.06		.95
FAGA066	5352	140.2	143.3	3.1	97	4A0	2.85	.06	.05	.61	3.0	.27				.66		.92
FAGA066	5353	144.8	147.8	3.0	100	4A0	2.89	.12	.06	.77	4.0	.34				.83		.93
FAGA066	5354	147.8	149.4	1.6	94	4C0	3.03	.12	.07	.10	4.0	.34				.17		.59
FAGA066	5355	149.4	152.4	3.0	87	4A0	2.82	.22	.04	.42	7.0	.34				.46		.91
FAGA066	5356	152.4	155.4	3.0	70	4A0	2.86	.10	.01	.40	3.0	.34				.41		.98
FAGA152	5359	93.3	94.8	1.5	93	4A3	2.85	.05	.13	.37	5.0	2.19				.50		.74
FAGA152	5360	94.8	96.3	1.5	87	4A3	2.81	.06	.17	.22	7.0	.21				.39		.56
FAGA152	5361	96.3	97.8	1.5	100	4A3	2.81	.05	.12	.15	6.0	.34				.27		.56
FAGA152	5362	97.8	99.3	1.5	93	4A3	2.99	.15	.07	.18	7.0	.48				.25		.72
FAGA152	5363	99.3	100.8	1.5	100	4A3	3.08	.14	.10	.34	7.0	.21				.44		.77
FAGA152	5364	100.8	101.8	1.0	100	4A3	2.90	.15	.05	.10	6.0	.21				.15		.67
FAGA152	5365	104.3	106.3	2.0	70	4A3	2.98	.16	.07	.21	5.0	.41				.28		.75
FAGA152	5366	106.3	108.3	2.0		4A3	2.87					.48						
FAGA152	5367	108.3	110.3	2.0	100	4A3	2.87	.07	.01	.15	3.0	.27				.16		.94
FAGA152	5368	110.3	112.3	2.0	100	4A3	2.82	.11	.01	.18	3.0	.27				.19		.95
FAGA152	5369	112.3	114.3	2.0	85	4A3	3.06	.13	.03	.55	5.0	.27				.58		.95
FAGA152	5370	114.3	116.3	2.0	80	4A3	2.90	.13	.02	.36	5.0	.21				.38		.95
FAGA152	5371	116.3	118.3	2.0	100	4A3	2.93	.07	.02	.38	3.0	.21				.40		.95
FAGA152	5372	118.3	120.3	2.0	100	4A3	2.89	.07	.01	.20	2.0	.21				.21		.95
FAGA152	5373	120.3	122.3	2.0	100	4A3	2.82	.16	.01	.51	5.0	.34				.52		.98
FAGA152	5374	122.3	124.3	2.0	95	4A3	2.85	.23	.01	.38	6.0	.34				.39		.97
FAGA152	5375	124.3	126.3	2.0	95	4A3	2.88	.18	.01	.68	5.0	.41				.69		.99
FAGA152	5376	126.3	128.3	2.0	100	4A3	2.91	.17	.01	.32	3.0	.21				.33		.97

DDH	SAMPLE	----DEPTHS----		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAO	PB+ZN	PO+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGA152	5377	128.3	130.3	2.0	50	4A3	2.82	.16	.02	.19	4.0	.27				.21		.90
FAGA152	5378	130.3	132.0	1.7	100	4A3	2.88	.10	.01	.25	4.0	3.02				.26		.96
FAGA152	5379	136.2	138.2	2.0	100	4A3	2.83	.15	.01	.19	4.0	.27				.20		.95
FAGA152	5380	138.2	140.2	2.0	90	4A3	2.90	.25	.01	.21	4.0	.34				.22		.95
FAGA152	5381	140.2	142.2	2.0	100	4A3	2.75	.15	.01	.09	2.0	.21				.10		.90
FAGA152	5382	142.2	144.2	2.0	85	4A3	2.80	.13	.01	.04	3.0	.21				.05		.80
FAGA152	5383	144.5	146.7	2.2	91	4A3	2.96	.12	.48	.77	10.0	.62	1.68	10.00		1.25	11.68	.62
FAGA152	5384	146.7	148.4	1.7	88	4D0	3.89	.23	1.70	3.32	29.0	1.23	1.89	27.90		5.02	29.79	.66
FAGA152	5385	148.4	150.9	2.5	92	4A0	2.88	.10	1.72	2.95	26.0	.48	1.84	6.90		4.67	8.74	.63
FAGA152	5386	175.3	177.3	2.0	95	4L1	3.08	.11	1.18	.91	12.0	.27	9.50	4.44		2.09	13.94	.44
FAGA152	5387	177.3	179.0	1.7	82	4L1	3.09	.08	2.45	1.88	23.0	.14	8.68	2.74		4.33	11.42	.43
FAGA152	5388	179.0	180.3	1.3	85	4L7	3.29	.15	2.26	3.10	25.0	.55	5.91	13.00		5.36	18.91	.58
FAGA152	5389	185.3	186.8	1.5	100	4A3	2.72	.03	.58	.88	9.0	.14				1.46		.60
FAGA152	5390	186.8	188.1	1.3	77	4A3	2.77	.06	.64	.94	11.0	.21				1.58		.59
FAGA152	5391	200.6	202.6	2.0	80	4EC8	3.98	.37	1.53	1.35	23.0	1.23	4.01	27.80		2.88	31.81	.47
FAGA152	5392	202.6	204.6	2.0	100	4C8	3.80	.36	.78	.95	18.0	.69	3.50	26.00		1.73	29.50	.55
FAGA152	5393	204.6	206.0	1.4	93	4GD4	3.76	.13	4.78	5.55	69.0	1.30	4.17	13.40		10.33	17.57	.54
FAGA200	5394	63.7	64.9	1.2	100	4A0	2.92	.15	.81	1.38	20.0	.07	2.77	8.80		2.19	11.57	.63
FAGA200	5395	64.9	66.1	1.2	92	4A0	2.91	.10	1.76	2.45	24.0	.55	1.01	10.40		4.21	11.41	.58
FAGA200	5396	66.1	67.7	1.6	94	4E4	4.44	.14	11.10	15.23	131.0	.69	.69	26.90		26.33	27.59	.58
FAGA200	5397	67.7	68.8	1.1	100	4A0	3.08	.14	.99	1.12	17.0	.75	.66	13.90		2.11	14.56	.53
FAGA200	5398	68.8	70.0	1.2	92	4A0	3.16	.18	1.10	1.28	22.0	.14	2.68	13.30		2.38	15.98	.54
FAGA200	5399	70.0	71.2	1.2	92	4E4	4.24	.13	10.90	19.68	141.0	1.23	4.03	18.60		30.58	22.63	.64
FAGA200	5400	71.2	72.5	1.3	100	4E4	4.52	.22	9.10	15.49	129.0	1.58	2.39	27.40		24.59	29.79	.63
FAGA201	5401	120.9	122.0	1.1	100	4G4	3.71	.07	4.15	6.50	72.0	.69				10.65		.61
FAGA201	5402	130.9	131.9	1.0	100	4C3	3.49	.10	1.75	1.83	38.0	.41				3.58		.51
FAGA201	5403	131.9	132.9	1.0	100	4C3	3.63	.25	.59	.43	20.0	.62				1.02		.42
FAGA201	5404	132.9	134.4	1.5	40	4A0	2.80	.06	.04	.04	4.0	.14				.03		.50
FAGA201	5405	134.4	135.9	1.5	47	4A0	2.92	.09	.04	.03	4.0	.34				.07		.43
FAGA201	5406	135.9	137.4	1.5	80	4A0	2.89	.04	.01	.02	2.0	.21				.03		.67
FAGA201	5407	137.4	138.9	1.5	93	4A0	2.86	.02	.04	.02	2.0	.07				.06		.33
FAGA201	5408	138.9	140.4	1.5	93	4A0	2.88	.06	.05	.02	5.0	.21				.07		.29
FAGA201	5409	140.4	141.9	1.5	93	4A0	2.82	.07	.16	.20	5.0	.55				.36		.56
FAGA201	5410	141.9	143.0	1.1	91	4C37	3.57	.19	.94	.68	20.0	.14				1.62		.42
FAGA201	5411	143.0	144.1	1.1	100	4C37	3.28	.17	.84	.45	19.0	.27				1.29		.35
FAGA201	5412	146.3	147.8	1.5	100	4A0	2.86	.05	.01	.03	3.0	.07				.04		.75
FAGA201	5413	147.8	149.3	1.5	100	4A0	2.86	.07	.07	.05	3.0	.14				.12		.42
FAGA201	5414	149.3	150.8	1.5	93	4A0	2.92	.04	.05	.06	3.0					.11		.55
FAGA201	5415	150.8	152.3	1.5	93	4A0	2.92	.04	.05	.04	2.0					.09		.44
FAGA201	5416	152.3	153.7	1.4	100	4A0	2.96	.04	.23	.20	4.0					.43		.47
FAGA201	5417	172.4	173.7	1.3	92	4C0	4.12	.37	1.71	1.36	31.0	1.37				3.07		.44
FAGA201	5418	173.7	174.6	.9	100	4A3	2.87	.03	.02	.04	2.0	.07				.06		.67
FAGA201	5419	186.0	187.1	1.1	100	4G4#	4.10	.19	5.03	4.87	80.0	.82	6.76	15.70		9.90	22.46	.49
FAGA201	5420	187.1	188.2	1.1	100	4C83	3.44	.12	2.54	2.77	36.0	.41	8.17	15.00		5.31	23.17	.52
FAGA201	5421	188.2	189.2	1.0	100	4E4#	3.70	.65	3.16	2.88	43.0	1.37	11.66	17.50		6.04	29.16	.48
FAGA201	5422	189.2	190.1	.9	100	4E4#	3.54	.17	3.21	3.15	41.0	.48	6.06	15.00		6.36	21.06	.50
FAGA201	5423	190.1	191.6	1.5	100	4C83	3.69	.24	1.68	1.09	39.0	.48	8.38	20.10		2.77	28.48	.39
FAGA201	5424	191.6	193.1	1.5	100	4C83	4.25	.36	1.94	1.29	41.0	.75	11.56	24.60		3.23	36.16	.40
FAGA201	5425	193.1	194.6	1.5	100	4C83	4.25	.29	1.56	1.02	35.0	1.03	8.76	26.80		2.58	35.56	.40
FAGA201	5426	194.6	196.1	1.5	100	4D83	4.15	.22	3.48	2.90	67.0	.89	8.44	27.80		6.38	36.24	.45

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAO	PB+ZN	PO+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGA201	5427	196.1	197.6	1.5	87	4C83	3.58	.23	1.06	.69	21.0	.27	9.63	20.00		1.75	29.63	.39
FAGA201	5428	197.6	199.1	1.5	93	4C83	3.71	.34	.74	.24	19.0	.55	10.24	20.60		.98	30.84	.24
FAGA201	5429	199.1	200.6	1.5	100	4C83	4.17	.36	1.76	.95	33.0	.39	10.42	25.00		2.71	35.42	.35
FAGA201	5430	200.6	202.1	1.5	93	4C83	4.15	.27	1.91	1.26	40.0	1.17	8.76	25.10		3.17	33.86	.40
FAGA201	5431	202.1	203.1	1.0	100	4C83	3.93	.12	.61	.22	17.0	.48	10.94	22.50		.83	33.44	.27
FAGA201	5432	203.1	204.0	.9	89	4C83	3.23	.08	.91	.44	16.0	.34	4.10	12.40		1.35	16.50	.33
FAGA201	5433	204.0	205.2	1.2	92	4A0	2.87	.13	.49	.76	11.0	.34				1.25		.61
FAGA201	5434	205.2	206.4	1.2	75	4A0	3.09	.15	.61	.42	13.0	.48				1.03		.41
FAGA201	5435	206.4	207.6	1.2	92	4A0	2.99	.18	1.05	.64	17.0	.62				1.69		.38
FAGA202	5436	40.6	41.5	.9	89	4A3	3.44	.27	1.81	2.55	29.0	.82	1.28	17.50		4.36	18.78	.58
FAGA202	5437	41.5	42.6	1.1	73	4D4	4.09	.22	8.85	14.10	116.0	1.44	2.56	19.80		22.95	22.36	.61
FAGA202	5438	42.6	43.7	1.1	91	4D4	4.80	.32	8.84	15.30	161.0	2.40	1.22	30.60		24.14	31.82	.63
FAGA202	5439	43.7	44.6	.9	100	4A3	3.21	.08	2.41	4.40	45.0	.62	1.43	12.00		6.81	13.43	.65
FAGA202	5440	44.6	45.4	.8	100	4L2	2.89	.02	.16	.48	2.0	.07	4.35	2.03		.64	6.38	.75
FAGA202	5441	105.7	107.2	1.5	93	4L4	2.91	.01	.46	.08	3.0	.14				.54		.15
FAGA202	5442	141.5	143.0	1.5	93	4A0	2.83	.06	.19	.45	3.0	.07				.64		.70
FAGA202	5443	143.0	144.5	1.5	87	4A0	2.94	.10	.03	.12	4.0	.14				.15		.80
FAGA202	5444	144.5	146.0	1.5	100	4A0	2.91	.15	.02	.10	4.0	.07				.12		.83
FAGA202	5445	146.0	147.5	1.5	100	4A0	2.90	.10	.09	.22	5.0					.31		.71
FAGA202	5446	147.5	149.2	1.7	94	4A3	3.56	.05	.03	.09	2.0					.12		.75
FAGA202	5447	150.4	151.8	1.4	100	4A0	2.93	.12	.15	.35	9.0	.21	2.71	6.60		.50	9.31	.70
FAGA202	5448	151.8	153.1	1.3	92	4A0	2.92	.04	.98	3.30	22.0	.27	1.32	5.40		4.28	6.72	.77
FAGA202	5449	153.1	153.6	.5	100	4G4	4.33	.27	5.00	4.90	76.0	1.58	1.28	31.70		9.90	32.98	.49
FAGA202	5450	153.6	155.1	1.5	100	4A4	3.08	.05	1.90	3.60	31.0	.41	3.25	6.40		5.50	9.65	.65
FAGA202	5451	155.1	156.6	1.5	100	4A4	2.95	.01	1.09	2.70	19.0	.14	4.28	3.53		3.79	7.81	.71
FAGA202	5452	156.6	158.0	1.4	100	4A4	2.93	.01	.80	2.09	17.0	.21	3.01	2.88		2.89	5.89	.72
FAGA202	5453	162.2	163.2	1.0	100	4L4	2.87	.01	.04	.09	3.0	.14				.13		.69
FAGA202	5454	163.2	164.3	1.1	100	4L4	2.88	.01	.33	.40	3.0	.21				.73		.55
FAGA202	5455	166.3	168.0	1.7	100	4L24	2.82	.02	.11	.14	3.0	.21	2.75	1.63		.25	4.38	.56
FAGA202	5456	168.0	168.8	.8	100	4C3	4.57	.21	4.55	3.69	59.0	1.30	2.67	30.90		8.24	33.57	.45
FAGA202	5457	168.8	170.4	1.6	87	4G4#	4.71	.11	9.70	9.50	119.0	1.30	2.29	22.00		19.20	24.29	.49
FAGA202	5458	170.4	172.0	1.6	94	4G4#	4.30	.17	6.00	7.50	105.0	1.23	1.38	18.00		13.50	19.38	.56
FAGA202	5459	172.0	173.6	1.6	100	4G4#	4.01	.09	5.30	7.00	80.0	.96	1.67	12.10		12.30	13.77	.57
FAGA202	5460	173.6	174.7	1.1	82	4E0#	4.00	.03	.72	.61	13.0	1.37	1.90	28.20		1.33	30.10	.46
FAGA202	5461	174.7	175.8	1.1	100	4E8#	4.63	.37	1.11	.51	17.0	1.30	6.83	32.10		1.62	38.93	.31
FAGA202	5462	175.8	176.8	1.0	100	4E8#	4.42	.41	.90	.12	15.0	1.23	5.78	32.40		1.02	38.18	.12
FAGA202	5463	176.8	178.3	1.5	100	4G4#	4.07	.12	3.80	1.18	33.0	1.17	1.69	26.50		4.98	28.19	.24
FAGA202	5464	178.3	179.8	1.5	93	4G4#	4.35	.18	8.66	7.05	104.0	1.71	5.06	22.00		15.71	27.06	.45
FAGA202	5465	179.8	181.4	1.6	94	4G4#	4.15	.14	4.43	6.99	75.0	.69	4.74	14.30		11.42	19.04	.61
FAGA202	5466	181.4	182.9	1.5	100	4C7	3.53	.44	1.61	1.47	28.0	1.30	10.33	11.80		3.08	22.13	.48
FAGA202	5467	182.9	184.4	1.5	80	4C7	3.74	.37	1.90	2.03	33.0	2.33	12.78	20.40		3.93	33.18	.52
FAGA202	5468	184.4	185.9	1.5	93	4C7	3.59	.78	1.07	1.41	23.0	.69	11.12	13.60		2.48	24.72	.57
FAGA202	5469	185.9	187.4	1.5	100	4C7	3.70	.22	1.51	2.82	23.0	.48	8.00	16.90		4.33	24.90	.65
FAGA202	5470	187.4	188.4	1.0	100	4C7	3.45	.23	.82	.43	12.0	.55	4.29	17.90		1.25	22.19	.34
FAGA202	5471	188.4	189.9	1.5	93	4L4	3.50	.42	.86	1.28	15.0	.75	8.93	14.10		2.14	23.03	.60
FAGA202	5472	189.9	191.4	1.5	100	4L4	3.32	.40	.60	1.02	12.0	.41				1.62		.63
FAGA202	5473	191.4	192.8	1.4	100	4L4	3.21	.31	1.16	2.14	20.0	.41				3.30		.65
FAGA202	5474	192.8	194.4	1.6	100	4C73	4.03	.09	.40	1.10	11.0	.48				1.50		.73
FAGA202	5475	194.4	196.0	1.6	100	4C73	4.16	.38	.39	.79	16.0	.62				1.18		.67
FAGA202	5476	196.0	196.9	.9	100	4L24	2.95	.13	.05	.07	2.0	.27				.12		.58

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAO	PB+ZN	PO+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGA202	5477	196.9	198.2	1.3	100	4L247	3.09	.08	1.27	1.14	19.0	.62				2.41		.47
FAGA202	5478	198.2	199.7	1.5	100	4L0	2.90	.01	.08	.10	3.0	.41				.18		.56
FAGA202	5479	199.7	201.2	1.5	100	4L0	3.09	.03	.08	.42	3.0	.14				.50		.84
FAGA202	5480	201.2	202.7	1.5	80	4L0	2.86	.01	.09	.08	3.0	.14				.17		.47
FAGA202	5481	202.7	204.2	1.5	100	4L0	2.89	.06	.09	.54	4.0	.14				.63		.86
FAGA202	5482	204.2	205.2	1.0	100	4L0	2.94	.01	.01	.09	1.0	.14				.10		.90
FAGA202	5483	205.2	206.2	1.0	100	4L0	2.86	.01	.01	.05	1.0	.07				.06		.83
FAGA202	5484	207.6	208.8	1.2	100	4L0	2.84	.01	.01	.02	2.0	.14				.03		.67
FAGA202	5485	208.8	210.0	1.2	92	4LC	2.92	.03	.33	.01	7.0	.14				.34		.03
FAGA202	5486	210.0	211.2	1.2	100	4L0	2.83	.04	.05	.01	9.0					.06		.17
FAGA202	5487	212.0	213.7	1.7	100	4L0	2.94	.10	.01	.04	3.0					.05		.80
FAGA202	5488	214.3	216.1	1.8	94	4LC	2.87	.02	.02	.03	1.0					.05		.60
FAGA203	5489	54.2	55.3	1.1	100	4A0#	2.91	.01	.16	.62	5.0	.07				.78		.79
FAGA203	5490	68.6	69.3	.7	86	4E4#	4.46	.17	9.20	8.90	118.0	1.85	1.61	27.10		18.10	28.71	.49
FAGA203	5491	69.7	71.2	1.5	100	4G4	4.35	.14	11.80	18.60	156.0	.75	1.39	19.10		30.40	20.49	.61
FAGA203	5492	71.2	72.7	1.5	100	4G4	4.56	.21	12.50	23.00	155.0	.89	1.56	18.10		35.50	19.66	.65
FAGA203	5493	72.7	74.2	1.5	100	4G4	4.56	.16	8.30	16.50	111.0	.75	.85	16.60		24.80	17.45	.67
FAGA203	5494	74.2	75.7	1.5	93	4G4	4.27	.26	4.10	6.60	83.0	1.37	1.22	28.10		10.70	29.32	.62
FAGA203	5495	76.2	77.4	1.2	100	4G0#4	3.76	.06	6.55	8.36	76.0	.69	1.55	17.60		14.91	19.15	.56
FAGA203	5496	77.4	78.7	1.3	92	4G0#4	4.57	.12	10.90	14.40	135.0	1.03	1.45	23.20		25.30	24.65	.57
FAGA203	5497	84.4	86.0	1.6	100	4A0	2.87	.02	.21	.31	5.0	.21				.52		.60
FAGA203	5498	86.0	89.2	3.2	47	4A0	2.92	.02	.79	1.68	14.0	.34				2.47		.68
FAGA203	5500	89.2	90.8	1.6	87	5D4*	2.93	.04	.51	.62	15.0	.21				1.13		.55
FAGA203	5501	104.2	105.9	1.7	94	4G4	3.43	.16	4.62	6.37	86.0	.27	3.78	12.80		10.99	16.58	.58
FAGA203	5502	105.9	106.8	.9	100	4A4	3.06	.05	2.67	3.68	40.0	.21	2.75	8.90		6.35	11.65	.58
FAGA203	5503	106.8	108.3	1.5	100	4G4#	4.67	.24	8.63	8.61	144.0	1.58	.69	23.20		17.24	23.89	.50
FAGA203	5504	108.3	109.8	1.5	100	4G0#	4.75	.34	5.80	8.30	119.0	1.51	.66	26.00		14.10	26.66	.59
FAGA203	5505	109.8	111.4	1.6	100	4G0#	4.50	.22	3.50	5.70	63.0	2.13	.95	26.10		9.20	27.05	.62
FAGA203	5506	111.4	112.4	1.0	100	4C3	4.62	.36	2.50	2.80	52.0	1.99	1.18	34.60		5.30	35.78	.53
FAGA203	5507	112.4	113.9	1.5	93	4A0	2.84	.03	.34	.54	10.0	.14	.73	6.90		.88	7.63	.61
FAGA203	5508	113.9	115.4	1.5	87	4A0	2.89	.11	.45	.53	12.0	.34	1.12	8.40		.98	9.52	.54
FAGA203	5509	115.4	116.9	1.5	87	4A0	2.83	.12	.25	.23	7.0	.21				.48		.48
FAGA203	5510	116.9	118.4	1.5	100	4A0	2.88	.06	.11	.10	7.0	.21				.21		.48
FAGA203	5511	118.4	119.9	1.5	100	4A0	2.85	.22	.04	.13	7.0	.21				.17		.76
FAGA203	5512	119.9	121.4	1.5	100	4A0	2.83	.03	.02	.03	4.0	.07				.05		.60
FAGA203	5513	121.4	122.9	1.5	100	4A0	2.90	.12	.02	.08	2.0	.21				.10		.80
FAGA203	5514	122.9	124.4	1.5	93	4A0	2.81	.08	.09	.21	6.0	.21				.30		.70
FAGA203	5515	124.4	125.4	1.0	100	4A3	3.32	.23	.40	.50	13.0	.27				.90		.56
FAGA203	5516	125.4	126.4	1.0	100	4A0	2.90	.11	.02	.02	4.0	.14				.04		.50
FAGA203	5517	126.4	127.2	.8	87	4K#	3.68	.14	.40	.27	17.0	.21				.67		.40
FAGA203	5518	127.2	128.3	1.1	82	4DLA	3.45	.20	1.18	1.09	25.0	.41				2.27		.48
FAGA203	5519	128.3	129.4	1.1	100	4L0	2.98	.11	.99	.62	17.0	.62				1.61		.39
FAGA203	5520	129.4	130.9	1.5	93	4GC#	3.35	.18	2.80	2.70	32.0	.48				5.50		.49
FAGA203	5521	130.9	132.3	1.4	86	4GC#	3.59	.17	1.71	1.62	26.0	.27				3.33		.49
FAGA203	5522	132.3	133.5	1.2	75	4A0	2.92	.08	.14	.06	5.0	.07				.20		.30
FAGA203	5523	133.5	134.7	1.2	50	4L2	2.98	.20	.11	.23	5.0	1.30				.34		.68
FAGA203	5524	134.7	136.0	1.3	62	4L2	3.06	.11	.30	.65	7.0	.27				.95		.68
FAGA203	5525	136.0	137.3	1.3	38	4L2	2.93	.02	.17	.23	3.0	.27				.40		.57
FAGA203	5526	184.9	186.3	1.4	93	4L2	2.94	.02	.07	.14	2.0	.07				.21		.67
FAGA203	5527	186.3	187.7	1.4	100	4L2	2.87	.03	.23	.16	3.0	.21				.39		.41

DDH	SAMPLE	----DEPTHS----		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAG	PB+ZN	PO+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGA203	5528	187.7	189.1	1.4	100	4L2	2.82	.02	.23	.18	3.0	.14				.41		.44
FAGA203	5529	189.1	190.8	1.7	94	4HL5	3.68	.19	1.93	2.02	27.0	.14				3.95		.51
FAGA203	5530	190.8	192.2	1.4	100	4L0	2.86	.01	.10	.26	2.0	.14				.36		.72
FAGA203	5531	192.2	193.2	1.0	90	4A0	2.83	.01	.01	.04	1.0	.14				.05		.80
FAGA203	5532	193.2	194.3	1.1	91	4A0	2.90	.01	.02	.02	1.0	.07				.04		.50
FAGA203	5533	197.5	198.9	1.4	100	4L2	2.80	.02	.12	.31	2.0	.07				.43		.72
FAGA203	5534	198.9	200.3	1.4	100	4L2	2.88	.02	.02	.06	1.0	.14				.08		.75
FAGA203	5535	200.3	201.7	1.4	100	4L2	2.85	.04	.05	.01	1.0	.07				.06		.17
FAGA203	5536	201.7	203.1	1.4	100	4L2	2.97	.02	.02	.02	1.0	.14				.04		.50
FAGA203	5537	203.1	204.5	1.4	100	4L2	2.94	.04	.02	.02	2.0	.14				.04		.50
FAGA203	5538	204.5	205.8	1.3	100	4L2	2.84	.04	.02	.02	2.0	.07				.04		.50
FAGA203	5539	206.5	207.4	.9	100	4G4	4.14	.17	5.00	5.60	74.0	.69	5.13	21.70		10.60	26.83	.53
FAGA203	5540	207.4	208.5	1.1	82	4D8	4.07	.25	3.90	3.90	55.0	.89	7.00	19.00		7.80	26.00	.50
FAGA203	5541	208.5	210.0	1.5	100	4D8	4.35	.21	3.35	2.96	40.0	.69	5.90	30.40		6.31	36.30	.47
FAGA203	5542	210.0	211.5	1.5	93	4C8	4.00	.30	1.28	.89	47.0	1.03	8.02	24.50		2.17	32.52	.41
FAGA203	5543	211.5	213.0	1.5	100	4D8	4.43	.29	3.39	2.80	47.0	.82	7.45	24.50		6.19	31.95	.45
FAGA203	5544	213.0	214.8	1.8	94	4D8	4.19	.32	3.22	2.89	61.0	1.10	7.13	22.60		6.11	29.73	.47
FAGA203	5545	214.8	216.0	1.2	100	4C8	4.21	.25	3.79	2.92	55.0	.82	9.01	22.80		6.71	31.81	.44
FAGA203	5546	216.0	217.2	1.2	100	4C8	4.26	.34	.73	.35	29.0	.82	8.35	30.30		1.08	38.65	.32
FAGA203	5547	217.2	218.4	1.2	100	4C8	4.35	.24	1.10	.56	35.0	.96	8.60	26.70		1.66	35.30	.34
FAGA203	5548	218.4	219.7	1.3	100	4C8	4.09	.31	1.31	.76	29.0	.89	7.70	21.50		2.07	29.20	.37
FAGA203	5549	219.7	221.5	1.8	100	4G4	4.43	.17	5.25	4.95	76.0	1.10	7.04	15.60		10.20	22.64	.49
FAGA203	5550	221.5	222.4	.9	100	4C8	3.78	.09	.62	.13	17.0	1.99	3.63	24.10		.75	27.73	.17
FAGA203	5551	223.2	224.9	1.7	100	4C0	2.92	.09	.29	.43	6.0	.48				.72		.60
FAGA203	5552	224.9	226.7	1.8	100	4A0	2.92	.11	1.06	.64	16.0	.82				1.70		.38
FAGA203	5553	226.7	227.5	.8	100	4C0	3.00	.17	.32	.38	9.0	.34				.70		.54
FAGA203	5554	227.5	229.0	1.5	100	4L2	2.84	.01	.01	.01	1.0	1.51				.02		.50
FAGA203	5555	229.0	230.5	1.5	100	4L2	2.82	.01	.01	.01	1.0	.96				.02		.50
FAGA203	5556	230.5	232.0	1.5	100	4L2	2.86	.07	.01	.04	1.0	.07				.05		.80
FAGA203	5557	232.0	233.5	1.5	100	4L2	2.93	.10	.14	.02	3.0	.21				.16		.13
FAGA203	5558	236.9	238.5	1.6	94	4L2	2.91	.11	.08	.03	3.0	.07				.16		.50
FAGA203	5559	238.5	240.1	1.6	100	4L2	2.89	.11	.30	.10	5.0	.21				.40		.25
FAGA203	5560	240.1	241.7	1.6	87	4L2	3.04	.23	.28	.08	5.0	.21				.36		.22
FAGA203	5561	241.7	243.3	1.6	100	4L2	2.96	.15	.07	.08	4.0	.21				.15		.53
FAGA203	5562	243.3	244.9	1.6	100	4L2	2.90	.15	.05	.06	4.0	.27				.11		.55
FAGA203	5563	244.9	246.7	1.8	94	4L2	2.87	.08	.02	.06	2.0	.14				.08		.75
FAGA203	5564	246.7	248.4	1.7	100	4A0	3.02	.17	.38	.27	10.0	.34				.65		.42
FAGA203	5565	248.4	249.6	1.2	100	4L2	2.91	.08	.05	.09	3.0	.07				.14		.64
FAGA203	5566	250.1	251.1	1.0	90	4L2	2.89	.08	.04	.09	4.0	.07				.13		.69
FAGA203	5567	251.1	252.1	1.0	70	4L2	2.96	.08	.05	.11	3.0	.07				.16		.69
FAGA203	5568	252.1	252.9	.8	88	4L1	2.95	.09	.15	.15	5.0					.30		.50
FAGA203	5569	252.9	254.0	1.1	91	4L2	2.91	.02	.33	.33	3.0					.66		.50
FAGA203	5570	254.0	255.1	1.1	91	4L2	2.88	.03	.02	.02	1.0					.04		.50
FAGA204	5580	100.5	102.0	1.5	100	4L2	2.94	.06	.69	.68	13.0	.27				1.37		.50
FAGA204	5581	102.0	103.5	1.5	100	4L2	2.85	.04	.42	.61	5.0	.14				1.03		.59
FAGA204	5582	103.5	105.0	1.5	100	4L2	2.85	.04	1.06	.32	10.0	.55				1.38		.23
FAGA204	5583	105.0	106.6	1.6	100	4L2	2.83	.03	.55	.26	6.0	.75				.81		.32
FAGA204	5584	106.6	108.2	1.6	69	4L2	2.88	.03	1.12	.51	13.0	.27				1.63		.31
FAGA204	5585	108.2	109.7	1.5	93	4A0	2.85	.04	.03	.05	2.0	.21				.08		.63

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAO	PB+ZN	PC+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGA204	5586	109.7	111.3	1.6	94	4A0	2.82	.03	.04	.13	1.0	.14				.17		.76
FAGA204	5587	111.3	112.1	.8	100	4C0	3.01	.07	.04	.17	4.0	.34				.21		.81
FAGA204	5588	112.1	113.6	1.5	100	4L2	2.88	.04	.06	.13	15.0	.21				.19		.68
FAGA204	5589	113.6	115.1	1.5	100	4L2	2.83	.02	.17	.10	4.0	.14				.27		.37
FAGA204	5590	115.1	116.7	1.6	100	4L2	2.91	.02	.43	.09	6.0	.41				.52		.17
FAGA204	5591	116.7	118.3	1.6	94	4L2	2.84	.01	.27	.15	4.0	.07				.42		.36
FAGA204	5592	135.6	136.9	1.3	100	4A0	2.98	.17	.13	.37	5.0	.75				.50		.74
FAGA204	5593	136.9	138.2	1.3	85	4A0	3.08	.15	.12	.56	5.0	.34				.68		.82
FAGA204	5594	138.2	139.5	1.3	62	4A0	2.93	.10	.18	.35	6.0	.34				.53		.66
FAGA204	5595	139.5	140.9	1.4	79	4A0	2.87	.07	.02	.32	2.0	.14				.34		.94
FAGA204	5596	140.9	142.3	1.4	100	4A0	3.02	.13	.02	.14	4.0	.48				.16		.87
FAGA204	5597	142.9	144.4	1.5	93	4A0	2.90	.04	.14	.26	4.0	.14				.40		.65
FAGA204	5598	144.4	145.9	1.5	100	4A0	2.92	.09	.10	.30	5.0	.21				.40		.75
FAGA204	5599	145.9	147.3	1.4	100	4A0	2.96	.11	.50	1.07	14.0	.41				1.57		.68
FAGA204	5600	147.3	148.7	1.4	100	4A0	2.91	.02	1.55	3.00	35.0	.41				4.55		.66
FAGA204	5601	148.7	150.1	1.4	86	4A0	2.93	.01	.69	1.53	14.0	.34				2.22		.69
FAGA204	5602	166.8	168.4	1.6	100	4L2	2.97	.05	1.23	1.05	15.0	.21				2.28		.46
FAGA204	5603	168.4	170.1	1.7	100	4L2	2.83	.06	.43	.22	9.0	.14				.65		.34
FAGA204	5604	171.7	172.6	.9	100	4G4	4.55	.02	4.30	6.50	59.0	.41				10.80		.60
FAGA204	5605	178.0	179.2	1.2	100	4A3	3.21	.02	2.60	4.40	43.0	.55	1.50	12.50		7.00	14.00	.63
FAGA204	5606	179.2	180.6	1.4	100	4G4	4.54	.16	5.80	8.70	98.0	1.58	.58	17.30		14.50	17.88	.60
FAGA204	5607	180.6	181.9	1.3	100	4G4	4.63	.07	5.10	8.50	76.0	.82	1.13	15.00		13.60	16.13	.63
FAGA204	5608	181.9	183.2	1.3	92	4E4	4.50	.21	2.70	2.40	33.0	1.10	3.40	33.80		5.10	37.20	.47
FAGA204	5609	183.2	184.5	1.3	92	4E0	4.33	.32	1.39	1.40	23.0	4.25	3.06	31.40		2.79	34.46	.50
FAGA204	5610	184.5	186.2	1.7	65	4G4#	4.27	.16	7.20	11.00	117.0	.41	1.87	20.00		18.20	21.87	.60
FAGA204	5611	186.2	187.5	1.3	100	4E0#	4.29	.27	2.11	2.60	35.0	3.09	2.90	30.30		4.71	33.20	.55
FAGA204	5612	187.5	188.8	1.3	92	4E0#	4.23	.26	.92	.56	20.0	1.03	4.09	31.40		1.48	35.49	.38
FAGA204	5613	188.8	190.0	1.2	100	4C8	4.41	.34	1.24	1.59	22.0	1.37	8.02	26.60		2.83	34.62	.56
FAGA204	5614	190.0	191.2	1.2	100	4C8	4.29	.20	.59	.23	12.0	1.17	3.64	30.80		.82	34.44	.28
FAGA204	5615	191.2	192.3	1.1	82	4D8	3.71	.25	3.40	3.80	53.0	1.30	3.22	20.20		7.20	23.42	.53
FAGA205	5616	65.2	66.2	1.0	100	4D3	3.95	.15	3.90	7.10	66.0	.96	1.20	23.40		11.00	24.60	.65
FAGA205	5617	66.2	67.5	1.3	100	4A0	2.90	.04	1.85	2.40	29.0	.62	.80	4.18		4.25	4.98	.56
FAGA205	5618	67.5	68.9	1.4	100	4A0	2.88	.03	.98	1.22	14.0	.34	.71	4.14		2.20	4.85	.55
FAGA205	5619	91.0	93.1	2.1	95	4A0	2.97	.01	.54	1.38	7.0	.62	3.33	4.50		1.92	7.83	.72
FAGA205	5621	93.1	94.4	1.3	85	4D43	4.01	.11	5.90	10.10	97.0	.96	1.52	19.30		16.00	20.82	.63
FAGA205	5622	94.4	95.3	.9	100	4E0	4.89	.27	1.20	3.00	41.0	1.10	3.37	34.90		4.20	38.27	.71
FAGA205	5623	95.3	96.6	1.3	100	4G4	4.86	.19	5.50	7.40	102.0	.89	1.84	31.50		12.90	33.34	.57
FAGA205	5624	96.6	97.9	1.3	92	4G4	4.39	.16	7.20	13.60	138.0	1.17	1.98	23.00		20.80	24.98	.65
FAGA205	5625	97.9	99.6	1.7	94	4EG4	4.89	.22	6.20	10.80	95.0	.69	2.92	31.70		17.00	34.62	.64
FAGA205	5626	99.6	101.2	1.6	94	4G4	4.71	.22	7.10	14.60	103.0	2.26	2.22	26.80		21.70	29.02	.67
FAGA205	5627	101.2	102.7	1.5	93	4AD	3.46	.07	3.50	5.20	52.0	.82	1.26	15.10		8.70	16.36	.60
FAGA205	5628	102.7	104.2	1.5	100	4A0	3.14	.16	.39	.99	15.0	.48	.83	16.80		1.38	17.63	.72
FAGA205	5629	104.2	105.7	1.5	100	4A0	3.03	.10	.08	.16	7.0	.21	.79	13.30		.24	14.09	.67
FAGA205	5630	105.7	107.2	1.5	100	4A0	3.05	.11	.07	.51	7.0	.21				.58		.88
FAGA205	5631	107.2	108.7	1.5	100	4A0	3.02	.11	.08	.83	7.0	.14				.91		.91
FAGA205	5632	108.7	110.2	1.5	100	4A0	3.06	.16	.39	2.21	31.0	.21				2.60		.85
FAGA205	5633	110.2	111.7	1.5	93	4A0	2.89	.06	.27	.41	9.0	.34				.68		.60
FAGA205	5634	111.7	113.2	1.5	100	4AC	2.86	.06	.20	.98	7.0	.41				1.18		.83
FAGA205	5635	113.2	114.7	1.5	100	4A3	3.37	.16	.19	1.35	13.0	.55				1.54		.88
FAGA205	5636	114.7	116.2	1.5	100	4A0	3.21	.18	.26	.89	14.0	.41				1.15		.77

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAC	PB+ZN	PO+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGA205	5637	116.2	117.7	1.5	93	4A0	2.93	.06	.16	.36	6.0	.27				.52		.69
FAGA205	5641	122.5	124.0	1.5	100	4A0	2.86	.05	.08	.30	6.0	.21				.38		.79
FAGA205	5642	124.0	125.5	1.5	93	4A0	2.97	.08	.05	.73	11.0	.21	1.52	10.90		.78	12.42	.94
FAGA205	5643	125.5	127.0	1.5	100	4A0	3.13	.13	.23	1.14	17.0	.82	2.11	14.80		1.37	16.91	.83
FAGA205	5644	127.0	128.5	1.5	100	4A3	3.41	.17	1.56	2.21	35.0		2.46	16.50		3.77	18.96	.59
FAGA205	5645	128.5	130.0	1.5	100	4A0	3.16	.13	1.58	1.75	39.0	.55	1.57	16.10		3.33	17.67	.53
FAGA205	5646	130.0	131.5	1.5	100	4A0	3.11	.06	2.31	1.62	42.0	.75	2.18	14.30		3.93	16.48	.41
FAGA205	5647	131.5	133.0	1.5	100	4A0	3.21	.12	1.65	1.44	31.0	.89	2.08	15.10		3.09	17.18	.47
FAGA205	5648	133.0	134.5	1.5	100	4A0	3.06	.13	.33	1.06	29.0	.89	1.61	16.30		1.39	17.91	.76
FAGA205	5649	134.5	135.9	1.4	100	4A3	3.31	.16	.36	.93	15.0	.48	1.79	17.70		1.29	19.49	.72
FAGA205	5650	135.9	137.1	1.2	100	4C3	3.63	.17	.13	1.85	8.0	.69				1.98		.93
FAGA205	5651	137.1	138.8	1.7	100	4A3	3.40	.14	.10	.47	7.0	.69				.57		.82
FAGA205	5652	138.8	140.5	1.7	100	4A3	3.32	.21	.32	1.08	14.0	.76				1.40		.77
FAGA205	5653	140.5	142.2	1.7	100	4A0	2.95	.24	.09	1.71	9.0	.34				1.80		.95
FAGA205	5654	142.2	143.9	1.7	100	4A0	3.04	.24	.13	1.76	14.0	.48				1.89		.93
FAGA205	5655	143.9	145.7	1.8	100	4A0	2.97	.27	.11	1.79	11.0	.41				1.90		.94
FAGA205	5656	145.7	147.4	1.7	100	4C3	3.43	.12	.84	1.92	21.0	.62				2.76		.70
FAGA205	5657	147.4	149.0	1.6	100	4A3	3.33	.64	.11	1.92	12.0	.48				2.03		.95
FAGA205	5658	149.0	150.6	1.6	100	4A0	2.94	.24	.04	1.30	6.0	.34				1.34		.97
FAGA205	5659	150.6	152.2	1.6	100	4A0	2.87	.13	.10	1.14	6.0	.27				1.24		.92
FAGA205	5660	152.2	153.8	1.6	100	4A0	2.84	.10	.05	1.18	6.0	.21				1.23		.96
FAGA205	5661	153.8	155.3	1.5	100	4A0	2.88	.13	.04	1.19	6.0	.21				1.23		.97
FAGA205	5662	155.3	156.5	1.2	100	4C0	3.12	.15	.05	.81	1.0	.41				.86		.94
FAGA205	5663	156.5	158.0	1.5	100	4A0	2.99	.15	.08	1.30	2.0	.21				1.38		.94
FAGA205	5664	158.0	159.5	1.5	100	4A0	2.87	.05	.08	.82	1.0	.14	1.90	8.20		.90	10.10	.91
FAGA205	5665	159.5	160.9	1.4	100	4A0	3.17	.16	.04	.97	4.0	.48	2.59	16.20		1.01	18.79	.96
FAGA205	5666	160.9	161.9	1.0	100	4E4	4.31	.39	1.22	3.80	30.0	1.44	2.14	31.90		5.02	34.04	.76
FAGA205	5667	161.9	162.9	1.0	100	4E4	4.35	.23	1.80	4.70	34.0	1.37	2.63	30.10		6.50	32.73	.72
FAGA205	5668	243.8	244.4	.6	100	4G4	3.76	.09	5.00	7.30	102.0	1.78	3.20	15.60		12.30	18.80	.59
FAGA205	5669	244.4	245.9	1.5	100	4C38	4.27	.37	1.72	1.71	40.0	1.10	7.27	30.60		3.43	37.87	.50
FAGA205	5670	245.9	247.5	1.6	100	4C38	3.99	.31	1.44	1.83	38.0	1.03	6.83	25.90		3.27	32.73	.56
FAGA205	5671	247.5	249.1	1.6	100	4CG	4.44	.34	1.94	3.20	38.0	1.44	5.48	31.90		5.14	37.38	.62
FAGA205	5672	249.1	250.7	1.6	100	4CG	4.23	.29	3.90	3.70	78.0	2.26	4.64	28.30		7.60	32.94	.49
FAGA205	5673	250.7	252.1	1.4	100	4G4	4.06	.45	5.30	7.50	100.0	1.44	4.91	20.90		12.80	25.81	.59
FAGA205	5674	257.8	258.8	1.0	100	4C38	4.04	.41	1.96	2.30	43.0	.89				4.26		.54
FAGA205	5675	258.8	259.9	1.1	91	4C38	3.60	.29	2.30	2.70	46.0	.82				5.00		.54
FAGA205	5676	266.9	268.2	1.3	100	4C38	3.63	.19	1.81	1.10	33.0	.55				2.91		.38
FAGA205	5677	268.2	269.9	1.7	100	4L2	2.95	.04	.17	.20	4.0	.14				.37		.54
FAGA205	5678	269.9	270.8	.9	89	4A0	3.19	.20	1.01	.52	32.0	.48				1.53		.34
FAGA206	5680	104.5	108.8	4.3	30	4EG4	4.01	.22	5.80	11.00	104.0	.82	2.12	19.70		16.80	21.82	.65
FAGA206	5682	126.8	129.8	3.0	27	4A0	2.67	.06	.14	.17	5.0	.82				.31		.55
FAGA206	5683	129.8	132.6	2.8	36	4A0	2.76	.05	.23	.42	7.0	.41				.65		.65
FAGA206	5684	132.6	133.1	.5	100	4C0	3.22	.13	.18	.70	5.0	.14				.88		.80
FAGA206	5685	201.9	203.6	1.7	88	4A3	2.90	.16	.18	.20	5.0	.41				.38		.53
FAGA206	5686	224.5	227.1	2.6	54	4D8	3.55	.14	2.70	2.90	39.0	.48	12.55	15.60		5.60	28.15	.52
FAGA206	5687	227.1	228.6	1.5	87	4D8	3.89	.14	4.00	3.50	41.0	1.30	7.99	20.90		7.50	28.89	.47
FAGA206	5688	228.6	229.7	1.1	100	4C83	3.91	.24	2.01	.99	30.0	1.44	10.57	25.20		3.00	35.77	.33
FAGA206	5689	229.7	231.1	1.4	100	4C83	3.91	.11	2.90	1.13	44.0	1.51	10.17	24.00		4.03	34.17	.28
FAGA206	5690	231.1	232.5	1.4	100	4C83	3.98	.21	.98	.62	24.0	2.19	8.66	27.60		1.60	36.26	.39

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAO	PB+ZN	PC+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGA206	5691	254.6	255.8	1.2	100	4ACL	3.27	.14	1.46	1.45	26.0	.55				2.91		.50
FAGA206	5692	255.8	256.8	1.0	100	4A0	2.86	.19	.56	.70	12.0	.96				1.26		.56
FAGA206	5693	256.8	257.9	1.1	100	4A0	2.99	.18	1.33	1.68	23.0	.55				3.01		.56
FAGA210	5694	66.4	67.9	1.5	93	4G4	4.60	.09	5.10	10.10	84.0	1.10	1.43	22.60		15.20	24.03	.66
FAGA210	5695	67.9	69.5	1.6	94	4G4	4.61	.05	3.00	6.60	58.0	2.13	.63	18.20		9.60	18.83	.69
FAGA210	5696	69.5	70.6	1.1	100	4D4	4.17	.13	8.20	15.50	114.0	.69	.59	18.70		23.70	19.29	.65
FAGA210	5697	70.6	71.8	1.2	92	4D4	3.95	.09	8.40	16.30	172.0	1.37	1.28	17.50		24.70	18.78	.66
FAGA210	5698	71.8	72.5	.7	100	4G4	4.41	.16	5.40	12.90	116.0	1.65	1.08	15.60		18.30	16.68	.70
FAGA210	5699	72.5	73.7	1.2	75	4EG	4.77	.09	1.71	4.30	30.0	5.07	1.47	32.40		6.01	33.87	.72
FAGA210	5700	73.7	74.9	1.2	92	4EG	4.70	.10	1.18	4.50	26.0	.96	4.41	30.30		5.68	34.71	.79
FAGA210	5701	74.9	76.3	1.4	100	4G4	4.60	.07	4.90	8.30	70.0	1.10	.68	18.70		13.20	19.38	.63
FAGA210	5702	76.3	77.7	1.4	100	4G4	4.76	.14	5.30	8.90	94.0	1.30	.95	19.90		14.20	20.85	.63
FAGA210	5703	77.7	79.1	1.4	100	4EG	4.82	.26	1.92	3.60	51.0	.69	3.24	36.90		5.52	40.14	.65
FAGA210	5704	79.1	80.5	1.4	86	4EG	4.78	.23	4.70	6.60	82.0	1.17	1.91	34.00		11.30	35.91	.58
FAGA210	5705	80.5	81.5	1.0	100	4DA4	4.78	.22	7.70	11.60	114.0	1.37	1.14	33.10		19.30	34.24	.60
FAGA210	5706	81.5	83.2	1.7	100	4D4	3.70	.12	6.30	8.00	92.0	1.23	1.06	18.40		14.30	19.46	.56
FAGA210	5707	83.2	85.3	2.1	100	4A4	3.44	.19	6.40	9.10	85.0	1.23	1.16	15.50		15.50	16.66	.59
FAGA210	5709	85.3	86.6	1.3	100	4E4	4.56	.24	9.80	20.10	122.0	2.06	1.65	24.10		29.90	25.75	.67
FAGA210	5710	86.6	88.4	1.8	100	4D4	3.54	.07	8.80	15.90	130.0	1.30	1.51	11.70		24.70	13.21	.64
FAGA210	5711	88.4	89.6	1.2	100	4A0	2.94	.16	.19	.31	10.0	.48	.78	13.60		.50	14.38	.62
FAGA210	5712	89.6	90.8	1.2	100	4A0	2.78	.14	.13	.32	5.0	.34	.67	9.80		.45	10.47	.71
FAGA210	5713	90.8	92.0	1.2	100	4A0	2.79	.17	.19	.26	9.0	.34				.45		.50
FAGA210	5714	92.0	93.2	1.2	100	4A0	3.12	.13	.06	.38	11.0	.48				.44		.00
FAGA210	5715	93.2	94.4	1.2	100	4A0	3.22	.13	.06	.38	7.0	.34				.44		.00
FAGA210	5716	94.4	95.7	1.3	100	4A0	3.15	.16	.06	.10	8.0	.41				.16		.00
FAGA210	5717	95.7	97.0	1.3	100	4A3	3.38	.20	.09	.40	11.0	.48				.49		.00
FAGA210	5718	97.0	98.3	1.3	100	4A0	2.96	.24	.07	.37	9.0	.41				.44		.84
FAGA210	5719	98.3	99.6	1.3	85	4A0	3.03	.19	.06	.68	8.0	.34				.74		.92
FAGA210	5722	108.5	110.1	1.6	87	4A0	2.99	.11	.95	2.20	27.0	.27				3.15		.70
FAGA210	5723	110.1	111.7	1.6	100	4A0	3.03	.09	.48	.78	18.0	.48				1.26		.62
FAGA210	5724	111.7	113.3	1.6	100	4A3	3.32	.17	.28	1.59	13.0	.62				1.87		.85
FAGA210	5725	113.3	114.0	.7	100	4EQ#	3.89	.19	.16	3.07	10.0	.55				3.23		.95
FAGA210	5726	114.0	115.6	1.6	100	4A0	2.96	.23	.07	1.22	11.0	.48				1.29		.95
FAGA210	5727	115.6	117.2	1.6	44	4A0	2.83	.14	.04	.16	7.0	.34				.20		.80
FAGA210	5728	117.2	118.8	1.6	100	4A0	2.79	.12	.08	.36	8.0	.27				.44		.82
FAGA210	5729	118.8	127.4	8.6	14	4A0	3.10	.25	.07	.71	11.0	.96				.78		.91
FAGA211	5735	53.3	55.3	2.0	100	4DE4	3.79	.04	8.10	20.10	138.0	1.30	2.71	13.60		28.20	16.31	.71
FAGA211	5736	55.3	57.3	2.0	100	4D43	3.62	.07	8.00	18.40	144.0	.69	2.45	12.20		26.40	14.65	.70
FAGA211	5737	57.3	58.6	1.3	100	4D43	3.70	.05	6.30	15.60	112.0	.62	1.84	14.30		21.90	16.14	.71
FAGA211	5738	58.6	59.7	1.1	100	4E4	4.55	.28	2.70	7.50	62.0	.65	2.91	34.80		10.20	37.71	.74
FAGA211	5739	59.7	60.8	1.1	100	4E0	4.82	.12	1.35	2.80	30.0	.82	2.42	41.60		4.15	44.02	.67
FAGA211	5740	60.8	62.4	1.6	100	4D43	3.83	.06	7.60	17.70	144.0	.41	2.07	14.40		25.30	16.47	.70
FAGA211	5741	62.4	63.6	1.2	100	4C3	3.56	.07	5.00	11.40	92.0	.69	.80	12.10		16.40	12.90	.70
FAGA211	5742	63.6	65.1	1.5	100	4C3	3.46	.05	3.20	6.10	58.0	.69	1.19	12.20		9.30	13.39	.66
FAGA211	5743	65.1	66.3	1.2	100	4G4	3.62	.02	4.70	10.40	82.0	.62	1.45	13.00		15.10	14.45	.69
FAGA211	5744	66.3	67.6	1.3	100	4D34	3.95	.05	6.40	16.40	120.0	1.10	3.02	15.40		22.80	18.42	.72
FAGA211	5745	67.6	68.9	1.3	100	4D34	4.20	.10	7.40	16.40	132.0	1.23	3.25	18.90		23.80	22.15	.69
FAGA211	5746	68.9	70.6	1.7	100	4E4	4.30	.16	8.20	17.10	134.0	1.92	3.02	19.80		25.30	22.82	.68
FAGA211	5747	70.6	72.0	1.4	100	4D435	3.78	.21	6.30	8.60	104.0	2.40	1.83	17.00		14.90	18.83	.58
FAGA211	5748	72.0	73.8	1.8	100	4C3	3.64	.26	.20	.45	12.0	1.03	1.79	24.30		.65	26.09	.69

DDH	SAMPLE	---DEPTHS---		INT M	REC %	ROCK UNIT	S.G.	CU %	PB %	ZN %	AG G/MT	AU G/MT	PO %	PY %	BAG %	PB+ZN %	PO+PY %	ZN RATIO
		FROM	TO															
FAGA211	5749	73.8	75.1	1.3	100	4A3	3.21	.15	.08	.51	10.0	.69	.75	15.50		.59	16.25	.86
FAGA211	5750	75.1	76.3	1.2	100	4A3	3.31	.18	.08	.54	12.0	.75				.62		.87
FAGA211	5751	76.3	78.3	2.0	100	4C35	3.32	.24	.08	.73	14.0	.89				.81		.90
FAGA211	5752	78.3	80.3	2.0	100	4C35	3.54	.28	.06	.35	14.0	.89				.41		.85
FAGA211	5753	80.3	81.5	1.2	100	4C35	3.55	.22	.14	1.00	17.0	.75	2.07	21.80		1.14	23.87	.88
FAGA211	5754	81.5	83.2	1.7	100	4C3	3.51	.31	.06	.33	9.0	.69	2.45	21.10		.39	23.55	.85
FAGA211	5755	83.2	84.4	1.2	100	4C35	3.66	.26	2.20	1.73	162.0	1.17	2.13	18.70		3.93	20.83	.44
FAGA211	5756	84.4	85.7	1.3	100	4C35	3.42	.15	3.20	3.20	45.0	1.17	1.55	16.60		6.40	18.15	.50
FAGA211	5757	85.7	87.7	2.0	100	4D354	3.62	.16	6.90	9.50	82.0	1.37	2.57	15.30		16.40	17.87	.58
FAGA211	5758	87.7	89.7	2.0	100	4D35	3.37	.08	3.40	4.50	55.0	1.58	1.15	15.50		7.90	16.65	.57
FAGA211	5759	89.7	91.2	1.5	100	4A0	3.49	.12	1.29	1.35	18.0	.96	1.42	19.90		2.64	21.32	.51
FAGA211	5760	91.2	92.8	1.6	100	4A0	3.19	.13	1.05	1.34	24.0	.69	1.66	14.40		2.39	16.06	.56
FAGA211	5761	92.8	94.5	1.7	100	4C3	3.53	.36	.75	.92	14.0	.82	2.30	21.60		1.67	23.90	.55
FAGA211	5762	94.5	96.3	1.8	100	4C3	3.56	.26	.43	.40	10.0	.69	2.85	21.00		.83	23.85	.48
FAGA211	5763	96.3	98.3	2.0	100	4A0	3.28	.15	.27	.61	8.0	.55				.88		.69
FAGA211	5764	98.3	100.3	2.0	100	4A0	3.36	.15	.40	.67	12.0	.69				1.07		.63
FAGA211	5765	100.3	102.3	2.0	100	4A0	3.38	.18	.95	1.32	22.0	.69				2.27		.58
FAGA211	5766	102.3	104.3	2.0	100	4A0	3.21	.16	.07	.28	8.0	.41				.35		.80
FAGA211	5767	104.3	106.3	2.0	100	4A0	3.29	.23	.07	.32	6.0	.48				.39		.82
FAGA211	5768	106.3	108.3	2.0	100	4A0	3.21	.15	.07	.17	6.0	.41				.24		.71
FAGA211	5769	108.3	110.3	2.0	100	4A0	3.48	.53	.10	.24	14.0	.55				.34		.71
FAGA211	5770	110.3	112.3	2.0	100	4A0	2.96	.27	.07	.37	10.0	.27				.44		.84
FAGA211	5771	112.3	113.0	.7	100	4A0	3.02	.34	.07	.60	8.0	.34				.67		.90
FAGA211	5772	113.0	114.0	1.0	100	4C0	3.19	.21	.06	.28	8.0	.27				.34		.82
FAGA211	5773	114.0	116.0	2.0	100	4A0	2.89	.09	.06	.33	4.0	.21				.39		.85
FAGA211	5774	116.0	118.0	2.0	100	4A0	2.97	.15	.07	.64	8.0	.27				.71		.90
FAGA211	5775	118.0	120.0	2.0	100	4A0	2.92	.13	.06	.37	6.0	.34				.43		.86
FAGA211	5776	120.0	122.0	2.0	100	4A0	2.85	.04	.01	.64	3.0	.21	2.93	4.12		.65	7.05	.98
FAGA211	5777	122.0	124.0	2.0	100	4A0	3.04	.15	.02	.59	4.0	.34	2.89	10.40		.61	13.29	.97
FAGA211	5778	124.0	125.7	1.7	100	4A0	3.22	.17	1.48	1.11	22.0	1.10	1.38	11.30		2.59	12.68	.43
FAGA211	5779	125.7	128.0	2.3	100	4E0	4.68	.40	2.50	1.16	40.0	1.44	1.18	40.20		3.66	41.38	.32
FAGA211	5780	128.0	129.7	1.7	100	4E4	4.67	.33	3.90	1.73	66.0	1.71	1.15	39.40		5.63	40.55	.31
FAGA211	5781	129.7	131.0	1.3	100	4E0	4.69	.42	1.41	1.42	30.0	1.58	2.01	41.50		2.83	43.51	.50
FAGA211	5782	131.0	132.3	1.3	100	4E0	4.85	.36	1.77	1.58	33.0	1.65	1.22	42.70		3.35	43.92	.47
FAGA211	5783	132.3	134.3	2.0	100	4EC	4.03	.23	1.23	1.21	32.0	1.30	2.21	29.40		2.44	31.61	.50
FAGA211	5784	134.3	136.0	1.7	100	4EC4	3.90	.23	3.20	3.90	56.0	1.71	1.53	25.40		7.10	26.93	.55
FAGA211	5785	136.0	138.0	2.0	100	4EA4	4.22	.25	3.70	4.10	87.0	1.85	1.25	26.70		7.80	27.95	.53
FAGA211	5786	138.0	140.0	2.0	100	4EA4	3.79	.29	2.60	4.30	63.0	1.92	1.31	29.70		6.90	31.01	.62
FAGA211	5787	140.0	141.6	1.6	100	4EA	4.33	.27	1.14	1.36	26.0	1.17	1.17	33.70		2.50	34.87	.54
FAGA211	5788	141.6	143.3	1.7	100	4EA4	4.19	.37	3.00	3.60	56.0	1.78	1.42	27.40		6.60	28.82	.55
FAGA211	5789	143.3	143.8	.5	100	4D74	3.80	.40	9.00	11.50	141.0	1.17	10.13	9.00		20.50	19.13	.56
FAGA211	5790	174.0	175.8	1.8	100	4CE84	3.93	.28	2.90	2.50	45.0	.14				5.40		.46
FAGA211	5791	202.0	204.2	2.2	100	4G4	4.21	.16	5.50	7.60	86.0	1.51	2.40	15.20		13.10	17.60	.58
FAGA211	5792	204.2	206.2	2.0	100	4E84	4.31	.32	3.80	3.29	60.0	1.44	7.99	27.00		7.09	34.99	.46
FAGA211	5793	206.2	208.1	1.9	100	4E84	4.14	.34	2.50	2.64	38.0	1.17	8.67	27.10		5.14	35.77	.51
FAGA212	5794	67.1	68.4	1.3	100	4G4	4.68	.09	4.40	8.34	62.0	.62	1.01	21.00		12.74	22.01	.65
FAGA212	5795	68.4	69.7	1.3	100	4G4	4.36	.07	6.20	11.85	104.0	1.17	1.37	18.00		18.05	19.37	.66
FAGA212	5796	69.7	71.0	1.3	100	4E4	4.70	.11	4.70	8.90	86.0	1.37	.70	19.60		13.60	20.30	.65
FAGA212	5797	71.0	72.3	1.3	100	4G4	3.78	.17	8.00	14.20	127.0	1.58	.99	16.90		22.20	17.89	.64
FAGA212	5798	72.3	74.1	1.8	100	4D3	3.78	.20	5.40	12.30	134.0	1.58	1.27	14.40		17.70	15.67	.69

DDH	SAMPLE	----DEPTHS----		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAO	PB+ZN	PC+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGA212	5799	74.1	74.9	.8	100	4G4	4.61	.05	3.50	7.70	64.0	.82				11.20		.69
FAGA212	5800	74.9	76.2	1.3	100	4D43	3.78	.07	3.90	19.20	179.0	1.44	2.26	8.20		23.10	10.46	.83
FAGA208	5801	76.7	77.6	.9	100	4D3	3.82	.39	3.40	3.00	60.0	.27	7.82	21.00		6.40	28.82	.47
FAGA208	5802	77.6	78.4	.8	100	4L2	2.84	.09	.14	.03	4.0	.14	1.50	3.54		.17	5.04	.18
FAGA208	5803	78.4	80.0	1.6	100	4C3	3.57	.23	1.08	.74	22.0	.34	4.02	16.50		1.82	20.52	.41
FAGA208	5804	80.0	81.6	1.6	100	4C3	3.87	.20	2.40	1.72	39.0	.55	3.16	25.50		4.12	28.66	.42
FAGA208	5805	81.6	82.7	1.1	100	4L2	3.09	.06	.83	.43	13.0	.21	1.71	10.70		1.26	12.41	.34
FAGA208	5806	82.7	83.5	.8	100	4GC4	4.09	.18	6.70	8.30	109.0	.82	2.23	18.00		15.00	20.23	.55
FAGA208	5807	83.5	84.2	.7	100	4D4	4.64	.22	5.80	8.70	99.0	6.58	3.21	32.10		14.50	35.31	.60
FAGA208	5808	84.2	85.6	1.4	100	4G4	4.45	.05	5.90	12.30	115.0	.75	.66	16.90		18.20	17.56	.68
FAGA208	5809	85.6	87.0	1.4	100	4G4	4.47	.10	4.70	7.57	77.0	.41	1.56	10.60		12.27	12.16	.62
FAGA208	5810	87.0	88.4	1.4	100	4G4	4.50	.05	5.70	8.23	80.0	1.44	.94	8.10		13.93	9.04	.59
FAGA208	5811	125.5	126.4	.9	100	4E4	4.00	.24	3.40	4.50	55.0	1.99				7.90		.57
FAGA208	5812	140.3	141.8	1.5	100	4A0	3.00	.07	1.08	2.53	20.0	.34				3.61		.70
FAGA208	5813	141.8	143.3	1.5	87	4A0	2.92	.08	.51	.81	10.0	.34				1.32		.61
FAGA208	5814	143.3	144.8	1.5	100	4A0	2.83	.07	.68	1.23	12.0	.41				1.91		.64
FAGA208	5815	144.8	146.3	1.5	60	4A0	2.87	.07	.95	1.95	16.0	.41				2.90		.67
FAGA208	5816	146.3	147.7	1.4	100	4A0	2.84	.07	.70	1.20	11.0	.41				1.90		.63
FAGA208	5817	147.7	149.1	1.4	100	4A0	2.82	.05	.63	1.25	11.0	.27	1.84	3.40		1.88	5.24	.66
FAGA208	5818	149.1	150.5	1.4	100	4A0	2.85	.07	.65	1.07	11.0	.21	1.49	4.83		1.72	6.32	.62
FAGA208	5819	150.5	153.3	2.8	64	4A0	2.86	.07	1.16	1.91	16.0	.34	1.36	3.87		3.07	5.23	.62
FAGA208	5820	153.3	154.7	1.4	100	4A0	2.77	.05	.31	.57	6.0	.27	1.33	3.30		.88	4.63	.65
FAGA208	5821	154.7	156.1	1.4	100	4A0	2.86	.07	1.02	2.30	14.0	.48	1.48	3.93		3.32	5.41	.69
FAGA208	5823	172.4	173.9	1.5	100	4D3	3.49	.20	3.40	3.93	59.0	1.51	2.02	17.10		7.33	19.12	.54
FAGA208	5824	173.9	175.3	1.4	93	4C3	3.55	.25	.58	.85	14.0	1.44	1.48	19.70		1.43	21.18	.59
FAGA208	5825	175.3	176.7	1.4	100	4C3	3.52	.33	1.42	1.81	18.0	1.10	1.40	20.90		3.23	22.30	.56
FAGA208	5826	176.7	178.1	1.4	100	4C3	3.64	.27	.37	.84	18.0	1.51	1.73	24.10		1.21	25.83	.69
FAGA206	5828	236.3	237.8	1.5	100	4L2	3.05	.14	.12	.25	5.0	.27				.37		.68
FAGA206	5829	237.8	239.3	1.5	100	4L2	3.06	.43	.07	.12	5.0	.14				.19		.63
FAGA206	5830	239.3	240.8	1.5	93	4L2	3.09	.18	.03	.03	3.0	.14				.06		.50
FAGA206	5831	240.8	242.3	1.5	33	4L2	2.99	.11	.04	.03	2.0	.07				.07		.43
FAGA206	5832	242.3	243.9	1.6	100	4L2	2.88	.02	.02	.03	1.0	.07				.05		.60
FAGA206	5833	243.9	245.5	1.6	50	4L2	2.93	.04	.01	.04	2.0	.07				.05		.80
FAGA206	5834	245.5	247.1	1.6	100	4L2	2.93	.08	.01	.06	1.0	.34				.07		.86
FAGA206	5835	248.4	249.6	1.2	100	4L2	2.90	.04	.01	.07	1.0	.07				.08		.87
FAGA206	5836	259.6	261.1	1.5	100	4L2	2.93	.07	.09	.11	4.0	.07				.20		.55
FAGA206	5837	261.1	262.6	1.5	100	4L2	2.91	.09	.14	.05	3.0	.07				.19		.26
FAGA206	5838	262.6	264.1	1.5	100	4L2	2.93	.07	.14	.21	2.0	.07				.35		.60
FAGA206	5839	264.1	265.6	1.5	100	4L2	2.99	.09	.24	.16	4.0	.14				.40		.40
FAGA206	5840	265.6	267.2	1.6	100	4L2	2.93	.07	.05	.13	4.0	.07				.18		.72
FAGA206	5841	267.2	268.8	1.6	100	4L2	2.96	.10	.13	.11	5.0	.14				.24		.46
FAGA206	5842	268.8	270.4	1.6	100	4L2	2.93	.09	.07	.19	3.0	.07				.26		.73
FAGA206	5843	278.2	280.1	1.9	79	4L2	2.97	.10	.08	.33	4.0	.07				.41		.80
FAGA212	5851	76.2	77.5	1.3	100	4D43	4.09	.08	7.70	18.40	141.0	1.37	1.33	17.40		26.10	18.73	.70
FAGA212	5852	77.5	79.1	1.6	100	4G4	4.63	.07	4.60	8.70	99.0	.89	.55	18.10		13.30	18.65	.65
FAGA212	5853	79.1	80.8	1.7	100	4G4	4.68	.09	4.50	8.10	98.0	.89	.36	17.20		12.60	17.56	.64
FAGA212	5854	80.8	82.8	2.0	100	4D0	3.64	.03	2.30	5.70	44.0	.55	.54	15.80		8.00	16.34	.71
FAGA212	5855	82.8	83.7	.9	100	4E4	4.51	.07	6.80	7.30	114.0	.88	3.16	14.60		14.10	17.76	.52
FAGA212	5856	83.7	85.6	1.9	100	4D4	3.52	.06	4.20	9.20	101.0	.75	.74	15.70		13.40	16.44	.69

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK	S.G.	CU	PE	ZN	AG	AU	PO	PY	BAO	PB+ZN	PC+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGA212	5857	85.6	86.3	.7	100	4G0	4.53	.04	2.30	5.80	42.0	.48	.54	16.60		8.10	17.14	.72
FAGA212	5858	86.3	88.7	2.4	100	4E4	4.37	.17	6.20	11.10	127.0	1.30	1.67	21.50		17.30	23.17	.64
FAGA212	5859	88.7	90.1	1.4	100	4E4	4.22	.04	5.80	11.10	101.0	1.23	1.33	26.90		16.90	28.23	.66
FAGA212	5860	90.1	91.6	1.5	100	4DE4	3.78	.06	8.80	13.80	142.0	.75	2.36	11.60		22.60	13.96	.61
FAGA212	5861	91.6	92.8	1.2	100	4A3	3.42	.18	.11	1.09	14.0	.75	2.19	20.00		1.20	22.19	.91
FAGA212	5862	92.8	94.0	1.2	100	4A3	3.49	.22	1.44	4.30	32.0	.75	3.86	17.50		5.74	21.36	.75
FAGA212	5863	94.0	96.1	2.1	100	4E4	4.56	.23	5.40	11.20	89.0	1.58	3.35	30.50		16.60	33.85	.67
FAGA212	5864	96.1	97.4	1.3	100	4D34	3.90	.12	5.10	8.80	86.0	1.23	2.88	19.80		13.90	22.68	.63
FAGA212	5865	97.4	99.4	2.0	100	4A0	3.29	.17	1.18	1.80	25.0	.69	1.84	16.10		2.98	17.94	.60
FAGA212	5866	99.4	101.4	2.0	100	4A0	3.23	.13	.17	1.22	13.0	.34	1.52	16.90		1.39	18.42	.88
FAGA212	5867	101.4	103.4	2.0	100	4A0	2.91	.12	.09	.50	7.0	.27				.59		.85
FAGA212	5868	103.4	106.1	2.7	100	4A0	2.69	.11	.36	.59	13.0	.27				.95		.62
FAGA212	5869	106.1	108.1	2.0	100	4A0	3.11	.16	.39	1.22	13.0	.34				1.61		.76
FAGA212	5870	108.1	110.1	2.0	100	4A0	3.02	.11	.32	.81	12.0	.48				1.13		.72
FAGA212	5871	110.1	112.2	2.1	95	4A0	3.16	.14	.24	.75	9.0	.34				.99		.76
FAGA212	5872	112.2	114.2	2.0	100	4A3	3.60	.22	.22	.80	11.0	.69				1.02		.78
FAGA212	5873	114.2	116.2	2.0	100	4A3	3.63	.23	.35	.91	11.0	.69				1.26		.72
FAGA212	5874	116.2	117.9	1.7	100	4A3	3.67	.22	.39	.62	14.0	.62				1.01		.61
FAGA212	5875	117.9	120.0	2.1	100	4A3	3.34	.26	.09	.54	13.0	.62				.63		.86
FAGA212	5876	120.0	122.0	2.0	100	4A0	3.02	.20	.05	.46	7.0	.34				.51		.90
FAGA212	5877	122.0	124.0	2.0	100	4A0	3.73	.30	.11	.75	11.0	.34				.86		.87
FAGA212	5878	124.0	127.1	3.1	100	4A0	3.10	.41	.11	.58	12.0	.21				.69		.84
FAGA212	5879	127.1	129.1	2.0	100	4C9	3.30	.22	.33	1.22	10.0	.41				1.55		.79
FAGA212	5880	129.1	131.1	2.0	100	4C9	3.21	.65	.04	.78	12.0	.48				.82		.95
FAGA212	5881	131.1	132.1	1.0	100	4C9	3.28	.83	.04	1.38	12.0	.41				1.42		.97
FAGA212	5882	132.1	134.1	2.0	100	4A0	3.19	.76	.05	1.51	12.0	.34				1.56		.97
FAGA212	5883	134.1	136.1	2.0	100	4A0	3.42	.43	.17	1.10	10.0	.34				1.27		.87
FAGA212	5884	136.1	138.1	2.0	100	4A0	3.05	.53	.03	1.10	9.0	.27				1.13		.97
FAGA212	5885	138.1	139.5	1.4	100	4A0	3.00	.12	.08	3.93	7.0	.14				4.01		.98
FAGA212	5886	139.5	140.9	1.4	100	4A0	3.19	.24	.06	.57	8.0	.34	2.46	15.30		.63	17.76	.90
FAGA212	5887	140.9	142.1	1.2	100	4C3	3.43	.29	.05	1.06	10.0	.48	3.24	18.50		1.11	21.74	.95
FAGA212	5888	142.1	143.2	1.1	100	4C3	3.79	.32	2.00	2.90	40.0	1.17	3.53	26.10		4.90	29.63	.59
FAGA212	5889	143.2	145.2	2.0	100	4E4	4.56	.42	1.36	3.80	29.0	1.23	3.48	31.60		5.16	35.08	.74
FAGA212	5890	145.2	147.2	2.0	100	4E4	4.67	.28	.90	4.70	20.0	1.17	3.66	37.40		5.60	41.06	.84
FAGA212	5891	147.2	149.2	2.0	100	4E0	4.75	.40	.77	2.60	18.0	1.23	3.24	40.80		3.37	44.04	.77
FAGA212	5892	149.2	151.2	2.0	100	4E4	4.78	.24	2.40	4.40	35.0	1.30	3.14	38.50		6.80	41.64	.65
FAGA212	5893	151.2	153.2	2.0	100	4E4	4.77	.23	3.00	4.89	51.0	1.58	3.01	37.70		7.89	40.71	.62
FAGA212	5894	153.2	154.7	1.5	100	4E0	4.75	.36	.90	1.32	23.0	1.58	2.43	42.00		2.22	44.43	.59
FAGA212	5895	154.7	156.2	1.5	100	4E4	4.71	.39	3.50	4.98	59.0	1.30	1.90	37.20		8.48	39.10	.59
FAGA213	5896	37.2	38.6	1.4	100	4E0	4.32	.33	2.80	1.76	67.0	.96				4.56		.39
FAGA213	5897	44.8	47.7	2.9	100	4EL	3.44	.16	1.16	.93	18.0	.41	8.45	15.40		2.09	23.85	.44
FAGA213	5898	47.7	49.0	1.3	100	4E4	4.59	.17	5.80	5.00	84.0	1.78	2.81	33.70		10.80	36.51	.46
FAGA213	5899	49.3	51.4	2.1	100	4E4	4.25	.09	7.10	7.40	108.0	1.23	2.55	32.30		14.50	34.85	.51
FAGA213	5900	52.6	53.3	.7	100	4C3	3.76	.19	1.80	2.90	27.0	1.17	3.29	21.50		4.70	24.79	.62
FAGA213	5901	53.3	54.9	1.6	100	4A3	3.29	.12	.97	1.76	20.0	.82	2.06	16.00		2.73	18.06	.64
FAGA213	5902	54.9	56.1	1.2	100	4E4	4.27	.16	6.20	7.80	114.0	1.71	2.58	24.80		14.00	27.38	.56
FAGA213	5903	56.1	57.3	1.2	100	4E4	4.27	.14	4.08	5.18	57.0	1.30	2.21	29.80		9.26	32.01	.56
FAGA213	5904	57.3	58.2	.9	100	4A3	3.35	.13	.43	.47	13.0	1.37	1.76	17.30		.90	19.06	.52
FAGA213	5905	58.2	59.2	1.0	100	4D3	3.73	.12	2.43	4.70	23.0	1.58	4.58	20.80		7.13	25.38	.66
FAGA213	5906	59.2	61.6	2.4	100	4E4	4.56	.27	3.59	4.80	54.0	1.30	2.85	35.10		8.39	37.95	.57

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAC	PB+ZN	PG+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGA213	5907	61.6	63.1	1.5	100	4L2	3.39	.14	1.00	1.33	13.0	.34	7.58	12.30		2.33	19.88	.57
FAGA213	5908	63.1	64.3	1.2	100	4L2	2.94	.04	.47	.80	9.0	.07	3.95	4.41		1.27	8.36	.63
FAGA213	5909	115.8	117.1	1.3	100	4DL	3.58	.10	3.89	5.08	73.0	.41				8.97		.57
FAGA213	5910	242.0	246.9	4.9	41	4EC	3.64	.20	2.50	2.40	36.0	.82	6.80	19.10		4.90	25.90	.49
FAGA213	5911	260.2	262.2	2.0	100	4E81	4.14	.22	2.72	2.01	40.0	1.44				4.73		.42
FAGA213	5912	272.0	273.6	1.6	100	4A0	2.96	.14	.39	.45	10.0	.34				.84		.54
FAGA213	5913	279.2	281.9	2.7	100	4A0	3.08	.05	.09	.06	7.0	.14				.15		.40
FAGA213	5914	281.9	283.1	1.2	100	4L0	3.08	.03	.26	.20	11.0	.21				.46		.43
FAGA209	5915	65.0	65.8	.8	100	4EG	4.84	.18	4.10	4.00	74.0	1.44	1.00	39.40		8.10	40.40	.49
FAGA209	5916	65.8	67.4	1.6	38	4G4	4.76	.34	5.30	8.40	101.0	1.78	.79	22.70		13.70	23.49	.61
FAGA209	5917	67.4	68.7	1.3	100	4E4	4.23	.48	4.40	4.90	89.0	2.13	1.20	38.40		9.30	39.60	.53
FAGA209	5918	68.7	69.9	1.2	100	4E4	4.80	.15	6.80	8.10	97.0	1.17	1.28	28.60		14.90	29.88	.54
FAGA209	5919	69.9	71.3	1.4	79	4G4	4.50	.13	6.00	10.80	94.0	1.03	.69	17.20		16.80	17.89	.64
FAGA209	5920	96.9	98.9	2.0	100	4A0	2.81	.07	.28	.50	5.0					.78		.64
FAGA209	5921	98.9	100.3	1.4	100	4A0	2.74	.06	.24	.30	4.0	.07				.54		.56
FAGA209	5922	100.3	101.4	1.1	100	4A0	2.93	.10	.28	.64	5.0					.92		.70
FAGA209	5923	110.9	112.1	1.2	100	4C3	3.31	.12	1.20	1.33	19.0	.34				2.53		.53
FAGA209	5924	112.1	113.6	1.5	100	4C3	3.49	.14	1.78	2.90	25.0	.27				4.68		.62
FAGA209	5925	117.1	119.1	2.0	100	4E0	4.35	.28	1.46	2.80	27.0	1.37	2.30	36.70		4.26	39.00	.66
FAGA209	5926	119.1	120.7	1.6	100	4E4	4.37	.35	2.60	4.10	48.0	1.51	1.90	34.40		6.70	36.30	.61
FAGA207	5927	99.3	100.2	.9	100	4A0	2.81	.07	.03	.12	4.0	.21				.15		.80
FAGA207	5928	100.2	101.0	.8	100	4L12	2.93	.06	.02	.41	4.0	.14				.43		.95
FAGA207	5929	101.0	102.4	1.4	100	4A0	2.82	.05	.04	.49	3.0	.21				.53		.92
FAGA207	5930	102.4	103.5	1.1	100	4L2	2.80	.04	.09	.26	2.0	.21				.35		.74
FAGA207	5931	103.5	104.5	1.0	80	4A0	2.81	.02	.01	.08	1.0	.69				.09		.89
FAGA207	5932	126.2	127.6	1.4	100	4A0	2.79	.11	.26	.38	8.0	.21				.64		.59
FAGA207	5933	127.6	128.9	1.3	100	4A0	2.77	.04	.70	.08	10.0	.41				.78		.10
FAGA207	5934	128.9	130.3	1.4	100	4A0	2.87	.10	.19	.12	2.0	.14				.31		.39
FAGA207	5935	130.3	131.0	.7	100	4L2	2.84	.01	.01	.05	1.0	.07				.06		.83
FAGA207	5936	131.6	133.0	1.4	43	4A0	2.86	.05	.02	.16	4.0	.27	3.88	6.10		.18	9.98	.89
FAGA207	5937	133.0	134.4	1.4	100	4A0	2.86	.07	.44	.64	8.0	.41	1.36	6.50		1.08	7.86	.59
FAGA207	5938	134.4	135.8	1.4	100	4A4	2.91	.02	2.60	3.20	29.0	.34	.81	5.30		5.80	6.11	.55
FAGA207	5939	135.8	137.2	1.4	100	4A0	3.03	.02	1.28	3.20	25.0	.21	1.54	8.10		4.48	9.64	.71
FAGA207	5940	137.2	138.5	1.3	100	4A4	3.04	.04	2.20	3.40	37.0	.17	2.76	7.20		5.60	9.96	.61
FAGA207	5941	151.2	152.1	.9	100	4L2	3.07	.10	1.30	1.13	18.0	.27				2.43		.47
FAGA207	5942	152.1	152.9	.8	100	4E4#6	4.55	.15	7.30	5.70	88.0	1.03				13.00		.44
FAGA207	5943	153.3	154.4	1.1	100	4G4	4.51	.10	7.40	9.30	99.0	.96				16.70		.56
FAGA207	5944	97.4	97.9	.5	100	4A0	2.91	.05	.06	.37	3.0	.41				.43		.86
FAGA056	6051	98.8	100.3	1.5	100	4A4	3.48	.08	4.99	6.63	60.0	1.17	2.05	11.51		11.62	13.56	.57
FAGA056	6052	100.3	102.6	2.3	100	4A4	3.51	.03	2.71	4.79	37.0	.82	.75	8.94		7.50	9.69	.64
FAGA056	6053	102.6	104.0	1.4	86	4A43	3.26	.02	1.76	3.69	26.0	.75	.74	9.10		5.45	9.84	.68
FAGA056	6054	106.1	107.3	1.2	100	4L14	3.27	.05	5.03	1.78	45.0	1.78	.55	4.77		6.81	5.32	.26
FAGA056	6055	107.3	108.4	1.1	100	4C5	3.96	.05	2.01	1.21	23.0	.89	.30	5.95		3.22	6.25	.38
FAGA056	6056	108.4	110.1	1.7	100	4L4	3.17	.06	1.37	2.81	18.0	.69	3.87	3.15		4.18	7.02	.67
FAGA056	6057	110.1	112.2	2.1	43	4D0	4.76	.09	2.54	6.17	37.0	.89	4.58	7.93		8.71	12.51	.71
FAGA056	6058	112.2	115.4	3.2	31	4L0	3.00	.01	.13	.38	2.0	.34	4.04	3.85		.51	7.89	.75
FAGA056	6059	115.4	118.3	2.9	59	4D5	3.09	.10	1.81	3.76	27.0	.82	2.09	7.91		5.57	10.00	.68
FAGA056	6060	118.3	119.5	1.2	100	4C5	2.84	.01	1.66	2.70	21.0	.27	1.25	.67		4.36	1.92	.62
FAGA056	6061	119.5	121.3	1.8	100	4A4	3.06	.03	1.86	4.43	27.0	.62	.95	7.97		6.29	8.92	.70

DDH	SAMPLE	----DEPTHS----		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAO	PB+ZN	PC+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGA056	6062	121.3	123.1	1.8	67	4A4	3.24	.04	1.76	4.72	29.0	.62	1.21	12.24		6.48	13.45	.73
FAGA056	6063	123.1	125.2	2.1	81	4A4	3.36	.04	2.93	5.80	53.0	.96	1.01	13.49		8.73	14.50	.66
FAGA056	6064	125.2	126.5	1.3	92	4D0	3.84	.03	1.80	3.92	41.0	1.92	2.70	24.36		5.72	27.06	.69
FAGA056	6065	126.5	128.3	1.8	100	4A4	3.40	.04	3.13	6.14	57.0	1.03	1.21	14.46		9.27	15.67	.66
FAGA056	6066	128.3	130.1	1.8	100	4A4	3.16	.06	1.86	4.10	36.0	.89	.88	10.39		5.96	11.27	.69
FAGA056	6067	130.1	132.3	2.2	68	4A0	2.97	.04	1.27	3.21	22.0	.62	.94	5.80		4.48	6.74	.72
FAGA056	6068	132.3	134.4	2.1	57	4D0	3.00	.08	2.74	5.24	38.0	1.03	1.18	4.07		7.98	5.25	.66
FAGA056	6069	134.4	135.6	1.2	83	4D0	3.05	.03	1.78	3.77	31.0	.75	1.03	6.42		5.55	7.45	.68
FAGA056	6070	135.6	137.7	2.1	57	4L14	2.94	.02	1.14	3.68	21.0	.34	2.43	3.20		4.82	5.63	.76
FAGA056	6071	137.7	139.3	1.6	100	4D0	3.23	.11	3.03	6.44	59.0	1.23	1.75	7.88		9.47	9.63	.68
FAGA056	6072	139.3	141.2	1.9	89	4D0	3.21	.05	3.17	5.24	46.0	1.71	2.16	7.48		8.41	9.64	.62
FAGA056	6073	141.2	142.9	1.7	82	4A4	3.15	.04	3.94	3.02	64.0	.41	1.00	8.63		6.96	9.63	.43
FAGA056	6074	144.3	145.0	.7	57	4L04	3.16	.06	2.55	5.24	40.0	.96	1.45	7.90		7.79	9.35	.67
FAGA056	6075	145.0	147.2	2.2	73	4D0	3.41	.03	2.81	5.02	48.0	.96	1.35	15.02		7.83	16.37	.64
FAGA056	6076	147.2	148.7	1.5	93	4C5	3.55	.05	.56	2.68	19.0	1.58	2.23	20.69		3.24	22.92	.83
FAGA056	6077	148.7	150.0	1.3	100	4C5	3.47	.14	.77	1.22	24.0	1.92	1.72	25.34		1.99	27.06	.61
FAGA056	6078	150.0	151.8	1.8	100	4A4	3.68	.10	3.69	3.64	52.0	2.19	1.38	17.59		7.33	18.97	.50
FAGA056	6079	151.8	153.3	1.5	80	4A4	3.85	.06	5.60	8.60	82.0	1.71	1.48	17.78		14.20	19.26	.61
FAGA056	6080	153.3	154.9	1.6	44	4LD	3.39	.06	1.00	4.57	17.0	1.37	4.85	12.70		5.57	17.55	.82
FAGA056	6081	154.9	156.9	2.0	100	4A4	3.39	.03	4.52	8.75	75.0	1.10	1.60	9.09		13.27	10.69	.66
FAGA056	6082	156.9	159.0	2.1	67	4A4	3.34	.02	2.93	6.59	49.0	1.10	1.67	10.37		9.52	12.04	.69
FAGA056	6083	161.4	163.1	1.7	88	4D4	3.64	.07	6.96	10.20	118.0	2.19	1.76	11.82		17.16	13.58	.59
FAGA056	6084	166.2	166.8	.6	100	4D4*	3.90	.05	7.19	16.00	127.0	1.03	3.80	12.86		23.19	16.66	.69
FAGA056	6085	167.9	168.6	.7	86	4A14	3.23	.02	4.17	7.32	66.0	1.10	2.00	8.50		11.49	10.50	.64
FAGA056	6086	168.6	170.0	1.4	100	4D4	3.46	.06	7.13	12.20	136.0	1.10	4.86	10.07		19.33	14.93	.63
FAGA056	6087	170.4	172.4	2.0	100	4D4	3.47	.06	6.92	12.50	123.0	1.65	3.41	7.38		19.42	10.79	.64
FAGA056	6088	172.4	173.7	1.3	92	4D0	3.27	.03	1.81	3.83	28.0	1.03	3.63	8.60		5.64	12.23	.68
FAGA056	6089	173.7	175.3	1.6	88	4D4	3.59	.04	6.38	11.60	109.0	1.30	3.18	11.17		17.98	14.35	.65
FAGA056	6090	175.3	176.4	1.1	100	4K4	3.84	.12	5.27	11.40	110.0	1.58	5.20	13.30		16.67	18.50	.68
FAGA056	6091	176.4	177.4	1.0	100	4D4@	3.78	.04	7.97	15.40	140.0	1.58	1.61	12.36		23.37	13.97	.66
FAGA056	6092	180.7	181.3	.6	83	4D4@	4.11	.24	2.52	10.50	118.0	2.26	4.37	22.31		13.02	26.68	.81
FAGA056	6093	184.5	185.5	1.0	80	4DK4	3.73	.04	2.98	7.29	65.0	1.10	1.59	19.12		10.27	20.71	.71
FAGA056	6094	186.0	187.2	1.2	100	4E14	4.11	.20	6.63	10.50	126.0	2.40	1.70	22.67		17.13	24.37	.61
FAGA056	6095	187.2	188.5	1.3	85	4D56	3.83	.21	5.43	4.58	84.0	2.19	1.42	22.47		10.01	23.89	.46
FAGA056	6096	188.5	189.8	1.3	100	4D56	4.33	.07	5.96	11.80	123.0	.69	1.22	27.00		17.76	28.22	.66
FAGA056	6097	189.8	190.7	.9	100	4G4	4.83	.11	8.19	16.70	170.0	1.78	.66	28.62		24.89	29.28	.67
FAGA056	6098	190.7	191.4	.7	100	4K64	4.34	.11	1.66	3.53	54.0	.96	1.56	32.92		5.19	34.48	.68
FAGA056	6099	191.4	192.9	1.5	87	4G4	4.78	.16	5.65	7.00	92.0	1.85	.97	35.63		12.65	36.60	.55
FAGA056	6100	192.9	194.8	1.9	95	4G4	4.67	.25	7.53	11.90	141.0	.13	1.36	30.50		19.43	31.86	.61
FAGA056	6101	194.8	196.2	1.4	100	4A4	3.13	.08	3.33	5.98	59.0	.75	2.27	6.54		9.31	8.81	.64
FAGA056	6102	202.4	203.6	1.2	25	4A1	2.97	.07	.78	1.16	15.0	.55	.65	7.80		1.94	8.45	.60
FAGA056	6103	203.6	206.7	3.1	10	4A1		.02	.16	.51	6.0					.67		.76
FAGA056	6104	257.1	258.6	1.5	93	4A0		.09	.15	.50	4.0					.65		.77
FAGA056	6105	258.6	260.1	1.5	87	4A0		.13	.08	.25	6.0					.33		.76
FAGA056	6106	260.1	261.7	1.6	94	4A0		.15	.03	.88	6.0					.91		.97
FAGA056	6107	261.7	263.2	1.5	100	4A0		.09	.05	.34	4.0					.39		.87
FAGA056	6108	265.2	265.8	.6	100	4A0	3.02	.10	.05	2.31	6.0	.21	3.39	7.56		2.36	10.95	.98
FAGA056	6109	265.8	266.8	1.0	100	4E4	3.95	.09	4.48	7.88	68.0	.96	1.80	23.00		12.36	24.80	.64
FAGA056	6110	266.8	268.3	1.5	87	4A0	3.36	.10	1.14	1.98	20.0	.27	2.71	13.97		3.12	16.68	.63
FAGA056	6111	297.2	298.3	1.1	100	4C0	3.79	.26	1.48	1.86	32.0	.69	1.86	19.51		3.34	21.37	.56

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAO	PB+ZN	PO+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGA056	6112	298.3	300.1	1.8	89	4D42	4.09	.10	4.49	5.47	85.0	1.03	5.11	19.59		9.96	24.70	.55
FAGA056	6113	300.7	302.1	1.4	71	4D24	3.90	.25	5.23	6.05	105.0	1.99	3.14	18.70		11.28	21.84	.54
FAGU019	6114	20.3	21.3	1.0	80	4E9*	4.59	.16	4.55	3.23	75.0	1.10	3.98	30.82		7.78	34.80	.42
FAGU019	6115	21.3	22.9	1.6	50	4C*	3.79	.16	1.60	1.50	39.0	.27	12.69	13.88		3.10	26.57	.48
FAGU019	6116	29.3	30.5	1.2	100	4C0	3.47	.12	1.74	1.88	33.0	.21	6.39	10.60		3.62	16.99	.52
FAGU019	6117	30.5	31.2	.7	100	4G*	4.48	.25	4.24	5.38	78.0	.62	2.55	25.07		9.62	27.62	.56
FAGU019	6118	31.2	33.4	2.2	100	4E8	4.59	.13	2.33	1.69	47.0	.89	5.44	28.22		4.02	33.66	.42
FAGU019	6119	33.4	34.8	1.4	93	4E48	4.66	.13	5.39	5.11	91.0	.75	2.35	19.22		10.50	21.57	.49
FAGU019	6120	34.8	36.6	1.8	100	4G48	4.62	.15	6.60	6.42	114.0	1.70	5.12	20.30		13.02	25.42	.49
FAGU019	6121	36.6	38.2	1.6	88	4G48	4.33	.06	8.37	8.95	140.0	.41	2.60	8.77		17.32	11.37	.52
FAGU019	6122	38.2	39.1	.9	100	4G2	4.01	.14	3.64	1.94	54.0	.48	12.53	15.29		5.58	27.82	.35
FAGU019	6123	39.1	40.6	1.5	93	4G2	4.26	.13	4.51	4.25	68.0	.41	5.61	22.01		8.76	27.62	.49
FAGU019	6124	40.6	42.6	2.0	100	4G4	4.57	.08	7.83	6.86	126.0	.41	2.31	6.61		14.69	8.92	.47
FAGU019	6125	42.6	44.6	2.0	100	4G4	4.69	.07	6.84	8.29	127.0	.34	3.27	8.62		15.13	11.89	.55
FAGU019	6126	44.6	46.6	2.0	95	4G4	4.48	.05	5.30	7.36	90.0	.41	3.09	10.05		12.66	13.14	.58
FAGU019	6127	46.6	48.5	1.9	100	4E48	3.82	.17	5.22	4.13	75.0	.41	10.05	22.77		9.35	32.82	.44
FAGU019	6128	48.5	49.0	.5	100	4EL	3.65	1.04	2.60	2.07	39.0	.34	10.20	13.25		4.67	23.45	.44
FAGA095	6129	57.0	57.9	.9	67	4A4	3.43	.05	4.99	8.99	75.0	1.10	1.82	12.78		13.98	14.60	.64
FAGA095	6130	57.9	58.8	.9	100	4D4	4.00	.06	11.20	20.00	160.0	1.78	1.88	15.01		31.20	16.89	.64
FAGA095	6131	58.8	60.4	1.6	56	4LD	3.14	.02	2.41	4.48	44.0	.62	.80	8.17		6.89	8.97	.65
FAGA095	6132	60.4	61.6	1.2	75	4A4	3.15	.02	2.20	3.17	36.0	.89	.74	8.54		5.37	9.28	.59
FAGA095	6133	61.6	63.0	1.4	71	4DE4	3.97	.12	5.24	8.75	98.0	1.23	1.49	18.11		13.99	19.60	.63
FAGA095	6134	63.0	63.8	.8	75	4LD	3.26	.04	3.43	6.66	52.0	.41	4.32	5.28		10.09	9.60	.66
FAGA095	6135	63.8	65.4	1.6	100	4A4	3.44	.10	4.46	8.18	75.0	.96	1.01	14.10		12.64	15.11	.65
FAGU014	6136	19.4	21.2	1.8	100	4E04	4.52	.17	7.56	5.45	105.0	1.30	4.68	26.58		13.01	31.26	.42
FAGU014	6137	21.2	21.9	.7	100	4C*	4.21	.35	.56	.50	33.0	2.26	4.20	23.94		1.06	28.14	.47
FAGU014	6138	21.9	23.7	1.8	100	4E*	4.46	.32	.35	.16	31.0	2.81	2.15	35.47		.51	37.62	.31
FAGU014	6139	23.7	24.9	1.2	100	4G#4	4.35	.16	5.01	5.36	80.0	1.58	3.88	25.82		10.37	29.70	.52
FAGU014	6140	25.5	26.5	1.0	100	4E0	4.51	.38	.52	.36	35.0	1.03	1.86	38.10		.88	39.96	.41
FAGU014	6141	26.5	28.7	2.2	100	4G84	4.59	.12	5.95	6.33	92.0	1.17	3.99	16.96		12.28	20.95	.52
FAGU014	6142	28.7	29.5	.8	100	4G4	4.70	.06	10.17	7.42	150.0	1.10	1.22	20.98		17.59	22.20	.42
FAGU014	6143	29.5	30.5	1.0	70	4C0	3.33	.12	1.44	1.74	22.0	.34	3.76	11.44		3.18	15.20	.55
FAGU014	6144	30.5	32.3	1.8	44	4C0	3.86	.13	1.40	1.70	20.0	.62	14.29	19.74		3.10	34.03	.55
FAGU014	6145	35.3	36.1	.8	100	4L2	3.37	.15	1.80	1.61	27.0	.21	9.96	8.18		3.41	18.14	.47
FAGU014	6146	36.1	37.3	1.2	100	4C8	3.42	.21	1.48	1.89	22.0	.41	4.49	16.06		3.37	20.55	.56
FAGU014	6147	37.3	38.7	1.4	100	4G48	4.65	.07	7.68	7.18	117.0	.41	2.51	7.03		14.86	9.54	.48
FAGU014	6148	38.7	40.7	2.0	100	4G48	4.57	.04	6.36	7.59	105.0	.27	2.11	6.38		13.95	8.49	.54
FAGU014	6149	40.7	42.7	2.0	100	4G48	4.58	.04	6.42	7.97	111.0	.27	1.10	4.40		14.39	5.50	.55
FAGU014	6150	42.7	44.7	2.0	100	4G48	4.58	.11	6.22	7.34	100.0	.34	1.42	11.60		13.56	13.02	.54
FAGU014	6151	44.7	45.2	.5	100	4C6	3.86	.20	2.53	1.82	45.0	.69	8.45	23.05		4.35	31.50	.42
FAGU004	6152	.2	1.4	1.2	100	4A2	3.04	.03	2.29	1.92	30.0	.75	.76	8.04		4.21	8.80	.46
FAGU004	6153	1.4	2.7	1.3	69	4A2	2.96	.11	1.56	2.38	22.0	1.10	1.30	5.78		3.94	7.08	.60
FAGU004	6154	2.7	4.8	2.1	95	4A2	2.97	.06	1.87	.41	19.0	.82	.48	7.24		2.28	7.72	.18
FAGU004	6155	4.8	6.8	2.0	100	4A2	2.99	.08	1.77	.39	17.0	.89	.42	7.79		2.16	8.21	.18
FAGU004	6157	15.5	16.8	1.3	92	4A4	3.60	.04	8.42	15.00	142.0	1.30	1.41	9.29		23.42	10.70	.64
FAGU004	6158	16.8	17.8	1.0	100	4D4	4.16	.02	11.00	21.00	171.0	1.51	1.98	13.64		32.00	15.62	.66
FAGU004	6159	17.8	19.0	1.2	100	4E4	4.44	.18	8.44	15.50	153.0	1.92	1.22	24.76		23.94	25.98	.65
FAGU004	6160	44.8	45.7	.9	100	4L4	3.28	.13	1.05	.82	12.0	.07	6.80	7.20		1.87	14.00	.44
FAGU004	6161	45.7	46.3	.6	100	4D0	3.60	.20	2.67	2.66	34.0	.69	9.35	13.11		5.33	22.46	.50
FAGU004	6162	46.3	47.9	1.6	100	4GE4	4.69	.08	9.19	6.51	122.0	1.78	1.83	24.86		15.70	26.69	.41

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAO	PB+ZN	PO+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGU004	6163	47.9	48.7	.8	88	4H0	3.64	.33	2.36	1.69	33.0	.21	24.28	10.25		4.05	34.53	.42
FAGU006	6164	2.4	4.2	1.8	100	4A14	2.99	.03	1.91	4.11	32.0	.69	.92	3.48		6.02	4.40	.68
FAGU006	6165	4.2	6.0	1.8	100	4A14	3.18	.03	1.98	3.96	34.0	.55	.85	4.28		5.94	5.13	.67
FAGU006	6166	9.1	10.4	1.3	100	4A14	3.77	.08	3.07	6.05	45.0	.75	1.04	3.68		9.12	4.72	.66
FAGU006	6167	10.4	12.4	2.0	100	4A14	3.52	.04	2.90	3.81	36.0	1.10	.82	3.77		6.71	4.59	.57
FAGU006	6168	12.4	14.4	2.0	100	4A14	3.79	.02	2.70	6.33	39.0	.82	1.06	1.96		9.03	3.02	.70
FAGU006	6169	19.4	20.6	1.2	100	4A4	3.53	.02	3.92	6.59	76.0	1.03	.88	9.02		10.51	9.90	.63
FAGU006	6170	20.6	21.8	1.2	100	4A4	3.28	.02	3.90	7.37	78.0	1.10	.99	10.10		11.27	11.09	.65
FAGU006	6171	21.8	23.8	2.0	100	4E24	4.80	.05	12.66	23.40	203.0	1.58	1.86	18.09		36.06	19.95	.65
FAGU006	6172	23.8	25.9	2.1	100	4E24	4.50	.09	10.44	21.50	197.0	1.78	1.78	17.47		31.94	19.25	.67
FAGU006	6173	25.9	28.0	2.1	100	4A14	3.27	.01	3.29	7.40	65.0	.89	1.01	8.89		10.69	9.90	.69
FAGU006	6174	28.0	28.6	.6	100	4E24	4.29	.01	8.76	18.60	163.0	1.37	1.80	19.66		27.36	21.46	.68
FAGU006	6175	28.6	30.3	1.7	100	4D24	3.92	.01	9.56	18.50	189.0	1.10	1.95	11.45		28.06	13.40	.66
FAGU006	6176	30.3	32.1	1.8	100	4D24	3.94	.02	8.15	15.20	147.0	1.44	1.90	16.04		23.35	17.94	.65
FAGU006	6177	32.1	33.1	1.0	100	4E4	4.42	.02	8.04	16.00	151.0	1.58	1.17	23.81		24.04	24.98	.67
FAGU021	6178	1.8	3.9	2.1	100	4A14	3.01	.05	2.93	3.90	37.0	.89	.72	4.53		6.83	5.25	.57
FAGU021	6179	3.9	5.9	2.0	100	4A14	3.19	.07	6.00	5.74	71.0	1.23	1.05	5.40		11.74	6.45	.49
FAGU021	6180	5.9	7.9	2.0	100	4A14	3.14	.07	5.35	6.93	64.0	1.03	1.14	3.84		12.28	4.98	.56
FAGU021	6181	7.9	9.9	2.0	100	4A14	3.14	.04	4.99	8.36	63.0	.96	1.32	3.05		13.35	4.37	.63
FAGU021	6182	9.9	11.9	2.0	100	4A14	3.14	.08	3.19	5.95	42.0	.96	.96	3.54		9.14	4.50	.65
FAGU021	6183	11.9	12.3	.4	100	4E24	4.18	.25	16.26	21.30	242.0	1.37	2.55	10.00		37.56	12.55	.57
FAGU021	6184	12.3	13.5	1.2	100	4D54	3.58	.07	7.53	11.94	114.0	1.37	1.46	10.00		19.47	11.46	.61
FAGU021	6185	13.5	14.8	1.3	100	4A4	3.24	.02	2.57	4.90	40.0	.82	.92	10.90		7.47	11.82	.66
FAGU021	6186	14.8	15.9	1.1	100	4E4	4.00	.11	9.22	18.94	156.0	2.13	1.59	17.70		28.16	19.29	.67
FAGU021	6187	36.4	38.0	1.6	100	4L2	3.06	.03	.54	.80	6.0	.34	4.74	5.10		1.34	9.84	.60
FAGU021	6188	38.0	39.6	1.6	100	4L2	3.20	.06	.58	.55	7.0	.55	6.21	5.90		1.13	12.11	.49
FAGU021	6189	39.6	41.8	2.2	100	4G4#	4.72	.12	7.56	6.88	105.0	.89	2.29	18.40		14.44	20.69	.48
FAGU021	6190	41.8	43.0	1.2	100	4E6#4	4.60	.12	11.21	5.98	113.0	.96	2.72	23.10		17.19	25.82	.35
FAGU021	6191	43.0	44.5	1.5	100	4L24	3.41	.16	1.99	1.33	24.0	.34	6.46	10.60		3.32	17.06	.40
FAGU021	6192	44.5	45.5	1.0	100	4G#1	4.14	.17	3.80	2.40	46.0	.41	10.96	21.90		6.20	32.86	.39
FAGU021	6193	45.5	45.9	.4	100	4L14	3.28	.12	1.57	1.15	19.0	.21	5.97	9.00		2.72	14.97	.42
FAGAG60	6194	100.0	100.9	.9	100	4L14	3.12	.04	1.49	2.50	22.0	.21	3.64	6.16		3.99	9.80	.63
FAGAG60	6195	100.9	102.4	1.5	100	4E14	4.24	.08	5.05	6.34	83.0	.69	2.26	24.04		11.39	26.30	.56
FAGAG60	6196	102.4	103.3	.9	100	4G14	4.56	.02	6.83	8.76	122.0	2.54	1.09	4.49		15.59	5.58	.56
FAGAG60	6197	103.3	104.1	.8	87	4L32	3.06	.11	1.85	2.15	50.0	.82	1.80	7.30		4.00	9.10	.54
FAGAG60	6198	104.1	105.8	1.7	88	4L*	2.97	.05	.12	.17	5.0	.07	4.38	1.74		.29	6.12	.59
FAGAG60	6199	105.8	107.2	1.4	100	4L*	3.05	.05	.69	.29	13.0	.27	4.91	3.13		.98	8.04	.30
FAGAG60	6200	107.2	109.4	2.2	100	4G4	4.40	.06	6.88	8.36	112.0	.41	2.13	10.70		15.24	12.83	.55
FAGAG60	6201	109.4	110.8	1.4	100	4G4	4.63	.06	7.19	7.38	107.0	.55	3.51	9.39		14.57	12.90	.51
FAGAG60	6202	110.8	111.7	.9	100	4L0	3.02	.06	.31	.43	7.0	.21	3.24	2.69		.74	5.93	.58
FAGAG60	6203	111.7	113.5	1.8	100	4D7	3.71	.15	3.22	2.45	41.0	.48	13.01	11.19		5.67	24.20	.43
FAGAG60	6204	113.5	114.4	.9	100	4G84	4.62	.04	6.27	7.60	97.0	.41	2.96	9.84		13.87	12.80	.55
FAGAG60	6205	114.4	116.3	1.9	100	4EG	4.49	.21	4.17	4.21	74.0	.21	3.27	20.73		8.38	24.00	.50
FAGAG60	6207	123.7	125.9	2.2	100	4L0	3.22	.10	.55	.50	8.0	.34	3.72	11.48		1.05	15.20	.48
FAGAG60	6208	125.9	127.3	1.4	86	4L0	2.92	.02	.04	.05	1.0	1.03	3.63	1.80		.09	5.43	.56
FAGAG60	6209	127.3	128.3	1.0	100	4L0	3.15	.08	.51	.63	8.0	.75	5.15	7.25		1.14	12.40	.55
FAGAG60	6210	128.3	130.4	2.1	100	4L0	2.67	.01	.04	.04	1.0	.34	3.93	1.67		.08	5.60	.50
FAGAG60	6211	130.4	132.4	2.0	95	4L0	3.02	.11	.14	.14	6.0	.14	3.74	4.36		.28	8.10	.50
FAGAG60	6212	132.4	133.7	1.3	100	4E4#	4.32	.24	3.25	3.32	61.0	1.37	3.41	28.59		6.57	32.00	.51
FAGAG60	6213	133.7	134.9	1.2	100	4E4#	4.48	.22	4.97	4.16	74.0	1.17	6.04	28.16		9.13	34.20	.46

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PC	PY	BAO	PB+ZN	PC+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGA060	6214	134.9	136.9	2.0	100	4G#	3.96	.12	4.81	4.79	61.0	1.58	2.76	23.04		9.60	25.80	.50
FAGA060	6215	136.9	137.6	.7	100	4L34	3.06	.06	.80	.97	10.0	.21	3.20	5.45		1.77	8.65	.55
FAGA060	6216	144.8	146.9	2.1	52	4E4	4.59	.13	11.40	16.86	207.0	1.58	1.92	18.89		28.26	20.81	.60
FAGA060	6217	179.8	180.6	.8	100	4E0	3.53	.12	1.50	2.09	27.0	.27	3.61	18.49		3.59	22.10	.58
FAGA060	6218	183.2	183.7	.5	100	4E*	3.82	.21	.90	1.17	30.0	.34	19.75	15.25		2.07	35.00	.57
FAGA060	6219	257.3	259.0	1.7	94	5B12		.04	.36	.45	6.0					.81		.56
FAGA060	6220	267.0	268.5	1.5	100	4A3	2.95	.03	.12	.36	5.0	.14	1.60	6.80		.48	8.40	.75
FAGA060	6221	268.5	270.5	2.0	85	4A3		.02	.07	.03	2.0					.10		.30
FAGA060	6222	270.5	272.6	2.1	100	4A3		.05	.02	.02	1.0					.04		.50
FAGA060	6223	272.6	274.3	1.7	100	4A3		.06	.02	.06	2.0					.08		.75
FAGA060	6224	274.3	276.3	2.0	100	4A3		.05	.01	.05	2.0					.06		.83
FAGA060	6225	281.0	283.0	2.0	100	4A3		.05	.21	.19	7.0					.40		.48
FAGA060	6226	283.0	285.0	2.0	100	4A3		.07	.10	.03	3.0					.13		.23
FAGA060	6227	285.0	286.7	1.7	100	4A3		.06	.42	.36	10.0					.78		.46
FAGA060	6228	286.7	287.4	.7	100	4E1	3.55	.20	1.70	1.90	29.0	3.29	5.25	16.20		3.60	21.45	.53
FAGA060	6229	322.5	323.3	.8	100	4A3	2.99	.04	.62	.53	13.0	.41	2.55	4.56		1.15	7.11	.46
FAGA060	6230	323.3	324.4	1.1	82	4G8	4.41	.14	3.33	2.69	50.0	.82	8.11	20.60		6.02	28.71	.45
FAGA060	6231	324.4	325.1	.7	100	4C0	3.66	.13	2.23	2.48	41.0	.75	4.20	15.90		4.71	20.10	.53
FAGA060	6232	325.1	326.8	1.7	100	4A3	3.06	.12	1.57	2.06	25.0	.75	1.23	7.95		3.63	9.18	.57
FAGA060	6233	326.8	328.6	1.8	100	4A3	3.06	.10	.85	.76	19.0	.82	1.56	9.01		1.61	10.57	.47
FAGA060	6234	328.6	330.1	1.5	93	4G8	4.22	.11	3.41	2.72	50.0	.62	7.90	22.20		6.13	30.10	.44
FAGA060	6235	330.1	331.1	1.0	100	4E8	3.86	.28	1.40	.84	35.0	.48	7.00	22.50		2.24	29.50	.38
FAGA060	6236	331.1	333.2	2.1	100	5B26		.05	.44	.40	12.0					.84		.48
FAGA060	6237	333.2	335.3	2.1	100	5B26		.06	.28	.22	12.0					.50		.44
FAGA060	6238	340.2	342.1	1.9	100	4A0	3.32	.05	.84	.40	21.0	.27	6.50	11.70		1.24	18.20	.32
FAGA060	6239	342.1	344.0	1.9	100	4A0		.02	.05	.12	3.0					.17		.71
FAGA060	6240	345.0	347.5	2.5	100	4C5		.01	.05	.03	7.0					.08		.38
FAGA060	6241	347.5	349.5	2.0	100	5A6		.01	.02	.02	2.0					.04		.50
FAGU002	6242	.0	1.1	1.1	73	4D42	3.75	.08	4.74	8.16	79.0	1.23	1.62	17.10		12.90	18.72	.63
FAGU002	6243	1.1	3.0	1.9	100	4A14	4.62	.05	3.15	5.90	59.0	1.37	2.18	19.20		9.05	21.38	.65
FAGU002	6244	3.0	3.9	.9	100	4D4	4.29	.02	5.09	8.48	83.0	.75	2.02	18.30		13.57	20.32	.62
FAGU002	6245	3.9	6.1	2.2	95	4A14	3.48	.03	4.89	9.75	99.0	.89	1.60	10.80		14.64	12.40	.67
FAGU002	6246	6.1	7.4	1.3	100	4A14	3.18	.02	1.72	5.90	42.0	.48	1.73	8.30		7.62	10.03	.77
FAGU002	6247	7.4	8.6	1.2	92	4A14	3.28	.02	2.40	6.43	45.0	2.19	6.90	5.10		8.83	12.00	.73
FAGU002	6248	14.0	14.5	.5	100	4E4	4.48	.10	6.60	20.04	158.0	1.44	2.07	19.00		26.64	21.07	.75
FAGU008	6249	24.8	27.0	2.2	100	4A1	3.05	.05	.69	1.38	17.0	.41	2.17	5.80		2.07	7.97	.67
FAGU008	6250	27.0	29.2	2.2	77	4A1	3.55	.03	.65	1.28	15.0	.27	2.54	4.97		1.93	7.51	.66
FAGU008	6251	29.2	31.2	2.0	45	4A1	3.18	.08	.99	2.00	24.0	.62	2.26	11.74		2.99	14.00	.67
FAGU008	6252	31.2	33.4	2.2	100	4L14	3.33	.04	1.79	3.07	26.0	.27	5.18	3.41		4.86	8.59	.63
FAGU008	6253	33.4	35.5	2.1	100	4L14	3.02	.03	2.04	3.25	31.0	.55	5.42	2.33		5.29	7.75	.61
FAGU008	6254	35.5	36.5	1.0	100	4A14	3.02	.05	3.46	6.90	58.0	.75	1.70	4.08		10.36	5.78	.67
FAGU008	6255	36.5	38.7	2.2	100	4L14	2.95	.04	1.70	4.36	37.0	.21	2.28	1.77		6.06	4.05	.72
FAGU008	6256	38.7	40.8	2.1	100	4L14	2.99	.04	1.99	3.98	38.0	.34	2.50	4.12		5.97	6.62	.67
FAGU008	6257	40.8	42.3	1.5	93	4E4	4.85	.16	7.10	13.67	112.0	1.10	.74	29.66		20.77	30.40	.66
FAGU008	6258	42.3	43.9	1.6	100	4E4	4.11	.06	6.18	12.76	104.0	1.10	1.25	21.45		18.94	22.70	.67
FAGA077	6259	115.1	115.8	.7	100	4L0	3.17	.14	.67	.68	16.0	.21	6.60	7.80		1.35	14.40	.50
FAGA077	6260	116.7	118.4	1.7	76	4C0	3.87	.19	1.81	1.65	31.0	.48	8.40	22.50		3.46	30.90	.48
FAGA077	6261	118.4	119.8	1.4	100	4E0	4.35	.18	2.80	1.63	47.0	.62	3.73	35.90		4.43	39.63	.37
FAGA077	6262	119.8	120.1	.3	67	4K4@	3.31	.54	1.96	2.70	59.0	1.44	4.85	10.90		4.66	15.75	.58
FAGA077	6263	120.1	121.6	1.5	100	4E42	4.05	.11	3.50	3.00	46.0	.41	2.58	29.80		6.50	32.38	.46

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAO	PB+ZN	PO+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGA077	6264	121.6	123.7	2.1	100	4E1@	3.61	.14	.74	.64	19.0	.41	2.00	24.00		1.38	26.00	.46
FAGA077	6265	174.5	175.0	.5	100	4D0	3.44	.18	2.30	1.99	33.0	.55	7.82	14.10		4.29	21.92	.46
FAGA077	6266	175.0	175.4	.4	75	4L2@	3.30	.12	1.22	1.12	23.0	.48	6.86	11.10		2.34	17.96	.48
FAGA077	6267	175.4	175.7	.3	100	4CE8	4.11	.23	.66	.68	22.0	.82	3.88	30.70		1.34	34.58	.51
FAGA077	6268	175.7	177.4	1.7	71	4A0	3.00	.03	.06	.06	3.0	.21	3.70	4.19		.12	7.89	.50
FAGA077	6269	177.4	178.1	.7	100	4A0	2.87	.05	.11	.14	4.0	.27	2.06	3.89		.25	5.95	.56
FAGA077	6270	178.1	178.6	.5	80	4E0	3.98	.16	1.54	1.12	34.0	1.37	3.51	30.30		2.66	33.81	.42
FAGA077	6271	178.6	179.2	.6	100	4L13	3.23	.13	.63	.58	13.0	.27	3.46	9.40		1.21	12.86	.48
FAGA077	6272	179.2	179.7	.5	100	4D@	3.43	.13	3.30	3.40	42.0	.41	5.12	12.90		6.70	18.02	.51
FAGA077	6273	179.7	180.7	1.0	100	4L23	3.22	.16	1.52	1.21	31.0	.34	3.32	10.70		2.73	14.02	.44
FAGA077	6274	180.7	181.8	1.1	82	4E8	4.02	.25	1.72	1.26	38.0	.62	7.28	28.00		2.98	35.28	.42
FAGA077	6275	181.8	182.3	.5	80	4CA	3.25	.09	.31	.22	9.0	.27	5.03	12.50		.53	17.53	.42
FAGA077	6276	182.3	182.7	.4	100	4A0	2.92	.03	.08	.04	4.0	.21	2.77	2.61		.12	5.38	.33
FAGA077	6277	182.7	184.1	1.4	100	4L0	2.88	.02	.01	.01	1.0	.21	2.32	1.75		.02	4.07	.50
FAGA077	6278	184.1	185.6	1.5	93	4L0	2.94	.02	.02	.07	1.0	.21	2.19	2.27		.09	4.46	.78
FAGA077	6279	185.6	186.2	.6	100	4A0	3.02	.05	.50	.60	9.0	.41	2.24	7.90		1.10	10.14	.55
FAGA077	6280	186.2	187.2	1.0	100	4E1	4.20	.13	.58	.18	18.0	1.03	1.94	38.10		.76	40.04	.24
FAGA077	6281	187.2	189.1	1.9	100	4L14	3.50	.12	1.97	2.07	26.0	.55	5.29	16.40		4.04	21.69	.51
FAGA077	6282	189.1	191.1	2.0	100	4L14	3.45	.12	1.93	2.04	25.0	.69	4.86	16.10		3.97	20.96	.51
FAGA077	6283	191.1	192.6	1.5	100	4L14	3.45	.10	1.80	1.93	23.0	.55	4.64	15.00		3.73	19.64	.52
FAGA077	6284	192.6	194.8	2.2	100	4L14	3.43	.20	2.30	2.80	29.0	.75	6.47	15.30		5.10	21.77	.55
FAGA077	6285	194.8	197.8	3.0	100	4L14	3.27	.11	1.84	1.50	23.0	.55	4.07	12.20		3.34	16.27	.45
FAGA077	6286	197.8	198.4	.6	100	4A0	3.02	.10	.67	.75	8.0	.55	2.95	6.20		1.42	9.15	.53
FAGA077	6287	198.4	199.8	1.4	100	4L14	3.78	.15	2.06	2.50	26.0	.55	5.70	17.50		4.56	23.20	.55
FAGA077	6288	199.8	202.1	2.3	100	4L14	3.67	.16	2.60	2.90	32.0	.89	6.70	16.90		5.50	23.60	.53
FAGA077	6289	202.1	203.5	1.4	100	4L14	3.28	.09	1.60	1.50	18.0	.27	5.30	11.30		3.10	16.60	.48
FAGA077	6290	203.5	204.7	1.2	100	4L12	3.25	.11	1.36	1.46	20.0	.21	4.90	9.80		2.82	14.70	.52
FAGA077	6291	237.3	237.5	.2	100	4E0	3.78	.02	.06	.03	7.0	.48	6.50	27.60		.09	34.10	.33
FAGA077	6292	237.5	238.3	.8	100	4A0	3.14	.05	.14	.23	5.0	.27	2.72	12.10		.37	14.82	.62
FAGA077	6293	238.3	238.7	.4	100	4E1*8	4.15	.12	3.30	1.40	59.0	.89	10.40	26.10		4.70	36.50	.30
FAGA077	6294	238.7	239.1	.4	100	4G08	4.24	.08	3.70	3.60	53.0	.21	7.66	27.90		7.30	35.56	.49
FAGA077	6295	239.1	239.6	.5	100	4CLA	3.53	.15	1.48	1.17	26.0	.62	2.06	20.10		2.65	22.16	.44
FAGA077	6296	239.6	240.2	.6	100	4L0	3.11	.13	.41	.08	9.0	.21	3.74	7.20		.49	10.94	.16
FAGA077	6297	240.2	241.5	1.3	100	4A1	3.25	.18	2.30	1.95	36.0	.89	4.44	21.90		4.25	26.34	.46
FAGA077	6298	241.5	243.8	2.3	57	4E68*	3.05	.15	3.50	3.30	51.0	.75	6.40	28.80		6.80	35.20	.49
FAGA077	6299	243.8	245.1	1.3	85	4E8*	3.90	.15	1.95	.86	39.0	.41	7.50	26.20		2.81	33.70	.31
FAGA077	6300	245.1	246.4	1.3	100	4E8*	3.30	.12	3.00	.50	53.0	.48	10.00	23.70		3.50	33.70	.14
FAGA077	6301	246.4	248.3	1.9	79	4AE	3.56	.04	.09	.10	5.0	.27	1.32	19.60		.19	20.92	.53
FAGA077	6302	251.3	252.2	.9	100	4A3		.01	.06	.02	5.0					.08		.25
FAGA077	6303	252.2	252.8	.6	100	4A0		.01	.03	.02	2.0					.05		.40
FAGA077	6304	258.0	259.6	1.6	69	4E51		.01	.06	.02	5.0					.08		.25
FAGA077	6305	259.6	261.2	1.6	69	4A0		.01	.07	.03	5.0					.10		.30
FAGU005	6306	2.7	4.7	2.0	100	4A1	2.89	.03	1.09	1.67	13.0	.27	1.44	1.66		2.76	3.10	.61
FAGU005	6307	5.9	8.0	2.1	100	4A0	2.96	.02	2.20	2.20	25.0	.48	1.64	1.56		4.40	3.20	.50
FAGU005	6308	8.0	10.0	2.0	100	4A0	2.89	.01	1.11	2.60	12.0	.27	1.05	1.10		3.71	2.15	.70
FAGU005	6309	11.1	12.9	1.8	100	4L14	3.02	.02	1.90	2.70	28.0	.48	1.27	5.11		4.60	6.38	.59
FAGU005	6310	12.9	14.9	2.0	100	4L14	2.94	.02	1.37	1.41	19.0	.41	1.82	3.33		2.78	5.15	.51
FAGU005	6311	14.9	16.9	2.0	100	4L14	3.04	.04	.86	1.26	14.0	.48	1.07	9.53		2.12	10.60	.59
FAGU005	6312	16.9	17.7	.8	100	4L14	3.04	.08	.87	1.61	14.0	.48	1.16	9.24		2.48	10.40	.65
FAGU005	6313	21.8	22.3	.5	100	4C0		.04	.57	.45	8.0					1.02		.44

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAO	PB+ZN	PC+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGU005	6314	24.8	25.4	.6	100	4L14	2.93	.03	2.90	.83	39.0	.21	1.80	.74		3.73	2.54	.22
FAGU005	6315	27.4	29.0	1.6	50	4E4	4.52	.23	6.20	11.90	85.0	2.61	3.00	26.00		18.10	29.00	.66
FAGU005	6316	29.0	30.5	1.5	87	4E4	4.90	.14	4.90	10.50	80.0	1.37	3.87	28.83		15.40	32.70	.68
FAGU005	6317	30.9	32.0	1.1	64	4E2	4.00	.05	.55	.98	21.0	.41	2.10	26.90		1.53	29.00	.64
FAGU005	6318	32.0	33.7	1.7	88	4E42	4.74	.14	4.20	9.70	88.0	1.23	3.90	29.60		13.90	33.50	.70
FAGU005	6319	34.9	36.1	1.2	100	4G4	4.14	.05	3.00	7.40	56.0	.89	.78	19.62		10.40	20.40	.71
FAGU005	6320	36.1	37.2	1.1	100	4G*	4.34	.03	2.50	5.60	53.0	.62	.57	22.20		8.10	22.77	.69
FAGU005	6321	37.2	37.8	.6	100	4G4	4.11	.04	5.20	8.60	57.0	.82	1.54	22.56		13.80	24.10	.62
FAGU005	6322	40.5	41.9	1.4	100	4G0	4.80	.02	2.40	5.80	36.0	.34	.33	16.07		8.20	16.40	.71
FAGU005	6323	41.9	44.0	2.1	86	4G0	4.25	.02	2.80	6.20	51.0	.89	.57	27.13		9.00	27.70	.69
FAGU005	6324	44.0	44.2	.2	100	4A14	3.53	.05	3.60	7.10	66.0	.96	.71	15.29		10.70	16.00	.66
FAGU005	6325	48.7	48.9	.2	100	4A13	4.15	.23	3.80	6.40	138.0	1.58	.58	26.12		10.20	26.70	.63
FAGU005	6326	48.9	49.7	.8	100	4D0	3.86	.04	2.50	4.80	50.0	.69	.60	21.10		7.30	21.70	.66
FAGU005	6327	49.7	51.1	1.4	86	4E46	4.46	.06	4.60	11.20	80.0	.75	.78	20.72		15.80	21.50	.71
FAGU005	6328	51.1	52.1	1.0	100	4G4	4.34	.03	3.40	8.40	65.0	.55	.51	15.39		11.80	15.90	.71
FAGU005	6329	52.1	54.3	2.2	95	4DG4	3.86	.05	3.50	8.40	67.0	1.30	.78	14.42		11.90	15.20	.71
FAGU005	6330	54.3	55.3	1.0	100	4D46	3.94	.09	7.50	16.60	130.0	1.17	1.12	16.60		24.10	17.72	.69
FAGU005	6331	55.3	57.1	1.8	100	4E4	4.82	.16	2.50	3.10	44.0	1.10	.75	35.85		5.60	36.60	.55
FAGU005	6332	57.1	58.3	1.2	100	4G4	4.64	.37	5.50	11.40	122.0	2.67	1.01	26.49		16.90	27.50	.67
FAGU005	6333	58.3	59.4	1.1	100	4E48	4.46	.24	4.40	7.00	68.0	1.71	1.83	27.37		11.40	29.20	.61
FAGU005	6334	59.4	61.8	2.4	100	4E0	5.04	.22	.63	.88	19.0	.89	1.07	40.43		1.51	41.50	.58
FAGU005	6335	61.8	63.5	1.7	94	4G4*	4.72	.35	7.80	16.40	136.0	2.06	2.10	21.10		24.20	23.20	.68
FAGU005	6336	63.5	65.0	1.5	100	4G4*	4.50	.31	7.40	16.30	131.0	2.54	2.00	22.70		23.70	24.70	.69
FAGU005	6337	65.0	66.4	1.4	100	4E14	4.50	.18	4.40	8.10	69.0	2.26	1.41	27.89		12.50	29.30	.65
FAGU005	6338	66.4	67.9	1.5	87	4E14	4.55	.24	3.70	4.70	65.0	1.65	.97	30.63		8.40	31.60	.56
FAGU005	6339	67.9	70.1	2.2	100	4AD4	4.35	.12	7.10	19.10	126.0	1.44	2.81	17.79		26.20	20.60	.73
FAGU005	6340	70.1	70.9	.8	100	4A4	3.41	.07	7.70	11.60	102.0	1.65	1.24	9.00		19.30	10.24	.60
FAGU005	6341	70.9	72.8	1.9	89	4A4	3.72	.04	5.80	8.60	89.0	1.99	1.28	15.32		14.40	16.60	.60
FAGU005	6342	72.8	74.0	1.2	100	4AC	3.53	.22	1.21	3.40	12.0	1.30	1.94	17.36		4.61	19.30	.74
FAGU005	6343	74.0	76.0	2.0	100	4A13	3.57	.15	.80	2.60	13.0	1.30	1.88	17.72		3.40	19.60	.76
FAGU005	6344	76.0	78.0	2.0	90	4A13	3.43	.22	.37	.81	14.0	.55	1.54	16.86		1.18	18.40	.69
FAGU005	6345	78.0	80.0	2.0	75	4A13	3.39	.29	.26	.40	18.0	.55	1.43	17.37		.66	18.80	.61
FAGU005	6346	80.0	81.0	1.0	100	4A13		.19	.22	.23	11.0					.45		.51
FAGA112	6347	110.4	112.3	1.9	100	4E4*	4.11	.04	10.40	13.50	178.0	.62	4.09	16.90		23.90	20.99	.56
FAGA112	6348	112.3	114.5	2.2	100	4G48	4.80	.09	6.40	8.90	116.0	.89	1.29	16.80		15.30	18.09	.58
FAGA112	6349	114.5	115.4	.9	100	4E4*	4.64	.08	5.10	7.30	91.0	1.44	1.03	30.80		12.40	31.83	.59
FAGA112	6350	115.4	117.2	1.8	94	4GE4	4.03	.11	7.20	9.90	128.0	1.10	1.01	17.20		17.10	18.21	.58
FAGA112	6351	117.2	119.5	2.3	100	4A43	3.50	.06	2.20	4.30	37.0	.89	1.05	17.10		6.50	18.15	.66
FAGA112	6352	119.5	121.3	1.8	100	4A3	3.63	.11	1.94	1.73	33.0	1.23	1.03	19.20		3.67	20.23	.47
FAGA112	6353	121.3	122.1	.8	75	4E42	4.69	.06	5.20	5.80	92.0	1.30	.97	34.30		11.00	35.27	.53
FAGA112	6354	122.1	124.1	2.0	100	4A3	3.48	.09	.72	1.36	16.0	.96	.75	18.10		2.08	18.85	.65
FAGA112	6355	124.1	125.6	1.5	93	4A3	3.46	.11	1.08	1.45	20.0	1.03	.88	17.90		2.53	18.78	.57
FAGA112	6356	125.6	127.5	1.9	100	4A3	3.68	.13	2.20	2.02	39.0	1.17	1.42	21.10		4.22	22.52	.48
FAGA112	6357	127.5	128.3	.8	75	4D42	3.49	.12	7.30	14.80	135.0	1.30	3.70	7.90		22.10	11.60	.67
FAGA112	6358	128.3	130.8	2.5	100	4A0	3.02	.05	.74	1.23	12.0	.34	2.84	5.50		1.97	8.34	.62
FAGA112	6359	141.0	142.0	1.0	100	4D0		.03	1.24	3.90	21.0					5.14		.76
FAGA077	6360	248.3	251.3	3.0	77	5A19		.01	.03	.03	2.0					.06		.50
FAGU010	6361	1.0	2.3	1.3	85	4D4	3.08	.03	3.90	8.80	86.0	.69	2.53	1.57		12.70	4.10	.69
FAGU010	6362	2.3	3.9	1.6	56	4A14	2.97	.03	2.10	4.60	46.0	.69	1.51	1.97		6.70	3.48	.69
FAGU010	6363	3.9	6.1	2.2	82	4L14	3.05	.03	3.30	8.00	67.0	.75	1.72	2.14		11.30	3.86	.71

DDH	SAMPLE	---DEPTHS---		INT.	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAC	PB+ZN	PO+PY	ZN
		FROM	TO	M.	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGU010	6364	6.1	8.3	2.2	91	4L14	3.09	.07	3.00	7.40	54.0	1.03	2.20	3.78		10.40	5.98	.71
FAGU010	6365	8.3	10.3	2.0	75	4L14	3.07	.08	3.90	5.10	71.0	.82	1.53	4.53		9.00	6.06	.57
FAGU010	6366	10.3	12.2	1.9	68	4LD4	3.37	.12	8.70	11.90	166.0	1.99	2.82	2.95		20.60	5.77	.58
FAGU010	6367	12.2	12.8	.6	100	4L0	4.07	.02	.28	.22	5.0	.21	4.02	1.44		.50	5.46	.44
FAGU010	6368	12.8	14.4	1.6	56	5B19	3.20	.01	.88	2.90	14.0	.27	1.77	.48		3.78	2.25	.77
FAGU010	6369	14.4	16.1	1.7	76	5B19	2.88	.01	.41	1.14	7.0	.14	3.03	1.72		1.55	4.75	.74
FAGU010	6370	16.1	18.1	2.0	60	4A1	2.97	.02	1.00	2.02	14.0	.14	4.47	2.18		3.02	6.65	.67
FAGU010	6371	38.2	39.6	1.4	43	4L14	3.14	.01	2.40	4.60	35.0	.55	3.15	7.05		7.00	10.20	.66
FAGU010	6372	40.8	42.9	2.1	62	4A4	3.34	.05	5.10	7.70	83.0	.89	2.21	11.59		12.80	13.80	.60
FAGU010	6373	42.9	44.4	1.5	73	4L14	2.95	.03	2.90	5.80	49.0	.55	1.57	2.53		8.70	4.10	.67
FAGU010	6374	50.4	52.5	2.1	95	4L1	3.74	.04	.99	1.63	19.0	.27	.95	6.10		2.62	7.05	.62
FAGU010	6375	53.4	55.4	2.0	100	4A14	3.28	.05	2.60	4.30	47.0	.62	.95	7.65		6.90	8.60	.62
FAGU010	6376	55.4	56.5	1.1	100	4A14	3.17	.02	3.80	8.20	69.0	.55	.94	6.54		12.00	7.48	.68
FAGU010	6377	56.5	57.1	.6	100	4E12	4.13	.08	7.80	14.30	133.0	1.17	3.23	16.17		22.10	19.40	.65
FAGU025	6378	58.0	59.4	1.4	100	4B0	2.85	.03	.79	1.52	13.0	.07	1.89	.89		2.31	2.78	.66
FAGU025	6379	62.5	64.2	1.7	94	4D4	3.09	.01	3.81	13.60	80.0	.55	3.31	.85		17.41	4.16	.78
FAGU025	6380	64.2	66.4	2.2	73	4L14	2.88	.01	1.70	5.00	35.0	.34	2.29	.98		6.70	3.27	.75
FAGU025	6381	66.4	68.5	2.1	90	4L14	2.85	.01	1.34	2.90	32.0	.21	1.86	1.02		4.24	2.88	.68
FAGU025	6382	68.5	70.6	2.1	86	4L14	2.84	.03	1.15	4.10	29.0	.14	1.77	1.01		5.25	2.78	.78
FAGU025	6383	70.6	72.7	2.1	71	4L14	2.82	.01	.78	2.15	21.0	.14	1.77	1.11		2.93	2.88	.73
FAGU025	6384	90.9	91.9	1.0	100	4A14	4.59	.04	2.90	5.00	49.0	.62	3.63	6.33		7.90	9.96	.63
FAGU025	6385	91.9	94.1	2.2	73	5D4a	3.00	.02	.77	2.10	12.0	.07	5.17	3.12		2.87	8.29	.73
FAGU025	6386	94.1	96.1	2.0	100	4A14	3.15	.02	2.50	4.80	39.0	.55	1.24	9.20		7.30	10.44	.66
FAGU025	6387	96.1	97.8	1.7	100	4A1	3.20	.04	1.29	3.10	29.0	.62	1.37	12.10		4.39	13.47	.71
FAGU025	6388	97.8	99.5	1.7	88	4A14	3.34	.07	3.20	3.80	47.0	.69	1.20	14.00		7.00	15.20	.54
FAGU025	6389	99.5	100.8	1.3	100	4E14	3.68	.15	7.30	14.20	118.0	1.51	2.01	12.20		21.50	14.21	.66
FAGU025	6390	100.8	102.0	1.2	92	4E14	4.44	.12	9.90	18.50	158.0	1.58	3.18	18.78		28.40	21.96	.65
FAGU026	6391	.0	1.8	1.8	83	4A3	3.69	.11	.55	.48	8.0	2.06	1.18	24.60		1.03	25.78	.47
FAGU026	6392	1.8	2.8	1.0	90	5D4a	3.39	.05	.22	2.91	4.0	.89	4.26	14.10		3.13	18.36	.93
FAGU026	6393	2.8	4.1	1.3	100	4D0	3.65	.05	1.27	4.07	14.0	.69	3.27	20.30		5.34	23.57	.76
FAGU026	6394	4.1	5.8	1.7	100	4D4	2.96	.02	3.35	7.67	40.0	.27	1.76	1.61		11.02	3.37	.70
FAGU026	6395	5.8	7.5	1.7	100	4D0	2.76	.03	2.01	4.28	17.0	.21	1.51	1.37		6.29	2.88	.68
FAGU026	6396	7.5	9.2	1.7	100	4D0	2.85	.02	1.71	3.72	11.0	.14	1.05	1.24		5.43	2.29	.69
FAGU026	6397	9.2	11.0	1.8	100	4D0	2.88	.03	1.80	4.12	15.0	.27	1.68	1.89		5.92	3.57	.70
FAGU026	6398	11.0	12.5	1.5	100	4D4	3.00	.06	3.29	7.55	42.0	1.10	1.40	2.76		10.84	4.16	.70
FAGU026	6399	12.5	13.9	1.4	100	4D4	3.01	.04	3.54	8.22	40.0	.55	1.11	3.05		11.76	4.16	.70
FAGU026	6400	13.9	15.4	1.5	100	4D4	3.00	.06	3.27	7.95	42.0	.75	1.54	2.93		11.22	4.47	.71
FAGU026	6401	15.4	17.4	2.0	90	4D4	2.96	.03	3.44	6.82	37.0	.55	1.44	1.93		10.26	3.37	.66
FAGU026	6402	17.4	19.4	2.0	100	4D0	2.89	.03	1.82	5.36	10.0	.21	1.93	2.03		7.18	3.96	.75
FAGU026	6403	19.4	21.4	2.0	100	4D4	3.12	.09	3.55	7.00	41.0	1.23	1.28	6.12		10.55	7.40	.66
FAGU026	6404	21.4	22.7	1.3	92	4D0	3.16	.08	3.67	6.23	45.0	.96	1.21	7.90		9.90	9.11	.63
FAGU026	6405	22.7	24.1	1.4	100	4C0	3.10	.07	1.30	3.62	13.0	.34	1.15	8.70		4.92	9.85	.74
FAGU026	6406	24.1	25.8	1.7	100	4C0	2.93	.03	1.16	3.34	4.0	.21	1.10	2.47		4.50	3.57	.74
FAGU026	6407	25.8	27.5	1.7	100	4C0	2.83	.01	1.16	1.41	4.0	.14	.93	1.36		2.57	2.29	.55
FAGU026	6408	27.5	29.3	1.8	50	4C0	2.80	.07	2.26	1.93	23.0	1.17	1.04	3.02		4.19	4.06	.46
FAGU026	6409	29.3	31.4	2.1	90	4D0	3.00	.10	1.74	4.15	17.0	.41	1.50	2.26		5.89	3.76	.70
FAGU026	6410	31.4	33.5	2.1	100	4D0	2.96	.11	1.82	4.09	23.0	.62	1.26	4.51		5.91	5.77	.69
FAGU026	6411	33.5	35.5	2.0	85	4C0	2.94	.06	2.05	1.94	17.0	1.10	1.07	4.86		3.99	5.93	.49
FAGU026	6412	35.5	37.0	1.5	100	4L\$	2.86	.03	.92	1.85	4.0	.21	.96	2.61		2.77	3.57	.67
FAGU026	6413	37.0	38.6	1.6	100	4L1\$	2.88	.07	1.09	2.14	5.0	.21	2.08	3.73		3.23	5.81	.66

DDH	SAMPLE	---DEPTHS---		INT M	REC %	ROCK UNIT	S.G.	CU %	PB %	ZN %	AG G/MT	AU G/MT	PO %	PY %	BAO %	PB+ZN %	PO+PY %	ZN RATIO
		FROM	TO															
FAGU026	6414	38.6	40.0	1.4	100	4L14	2.90	.04	2.83	4.30	51.0	.34	1.30	2.34		7.13	3.64	.60
FAGU026	6415	48.1	49.7	1.6	100	4A24	3.22	.07	3.57	8.56	58.0	.89	3.84	7.50		12.13	11.34	.71
FAGU026	6416	49.7	50.3	.6	83	4L14	3.09	.03	3.46	8.05	58.0	.41	4.07	4.61		11.51	8.68	.70
FAGU026	6417	50.3	52.4	2.1	100	4A14	3.14	.02	3.22	8.37	60.0	.55	3.26	6.00		11.59	9.26	.72
FAGU026	6418	52.4	54.1	1.7	94	4A4	3.21	.04	3.72	6.43	49.0	.89	1.63	9.40		10.15	11.03	.63
FAGU026	6419	54.1	55.9	1.8	100	4A4	3.26	.08	4.66	9.00	66.0	.96	2.02	8.30		13.66	10.32	.66
FAGU026	6420	55.9	57.1	1.2	100	4D0	2.99	.04	1.22	4.14	58.0	.48	4.37	3.41		5.36	7.78	.77
FAGU026	6421	57.1	58.2	1.1	91	4C0		.05	1.43	1.35	22.0					2.78		.49
FAGU026	6422	58.2	59.1	.9	33	4D4	3.47	.06	4.27	6.93	58.0	.82	1.02	13.70		11.20	14.72	.62
FAGU013	6423	16.8	18.3	1.5	100	4E4	4.21	.12	4.01	5.65	61.0	1.17	1.33	28.77		9.66	30.10	.58
FAGU013	6424	18.3	19.4	1.1	100	4E4\$	4.56	.15	6.14	1.26	117.0	1.58	2.11	24.59		7.40	26.70	.17
FAGU013	6425	19.4	21.3	1.9	100	4E4	4.62	.16	7.06	8.56	121.0	1.23	1.07	29.43		15.62	30.50	.55
FAGU013	6426	21.3	23.1	1.8	100	4E4	4.51	.15	3.79	4.53	70.0	.96	.82	32.98		8.32	33.80	.54
FAGU013	6427	23.1	24.9	1.8	100	4E4	4.65	.16	4.06	6.04	61.0	1.57	.77	33.63		10.10	34.40	.60
FAGU013	6428	24.9	25.9	1.0	80	4G4\$	4.21	.14	4.95	7.57	99.0	1.23	.98	24.42		12.52	25.40	.60
FAGU013	6429	25.9	27.5	1.6	38	4E41	4.08	.04	10.30	18.20	141.0	.75	4.11	14.39		28.50	18.50	.64
FAGU013	6430	55.4	57.2	1.8	100	4D45	3.61	.16	5.67	8.46	89.0	.82	2.00	14.50		14.13	16.50	.60
FAGU013	6431	57.2	59.5	2.3	87	4D45	3.66	.28	4.30	6.11	73.0	1.65	2.87	19.33		10.41	22.20	.59
FAGU013	6432	59.5	60.4	.9	67	4A0	2.92	.05	1.34	3.39	21.0	.27	2.57	2.75		4.73	5.32	.72
FAGU013	6433	60.4	62.5	2.1	71	4D5	3.59	.11	4.79	3.91	74.0	1.78	1.53	19.67		8.70	21.20	.45
FAGU013	6434	62.5	64.4	1.9	95	4C5	3.62	.26	.89	.69	18.0	1.37	.96	24.94		1.58	25.90	.44
FAGU013	6435	64.4	66.3	1.9	100	4C5	3.53	.21	.93	.96	21.0	1.23	1.14	23.36		1.89	24.50	.51
FAGU013	6436	66.3	68.6	2.3	70	4C5	3.40	.19	.15	1.39	7.0	1.23	1.16	21.14		1.54	22.30	.90
FAGU013	6437	68.6	71.6	3.0	73	4D5	3.45	.18	2.76	3.28	42.0	1.65	1.44	19.26		6.04	20.70	.54
FAGU013	6438	77.4	78.6	1.2	75	4E41		.16	11.30	18.30	162.0					29.60		.62
FAGU013	6439	148.4	149.0	.6	100	4A0	2.83	.06	.42	.60	10.0	.55	.83	5.67		1.02	6.50	.59
FAGU013	6440	149.0	150.6	1.6	100	4C0	3.79	.20	1.01	.86	20.0	.82	3.37	24.40		1.87	27.77	.46
FAGU013	6441	150.6	152.5	1.9	100	4A0	2.98	.08	.77	.84	10.0	.41	2.32	7.22		1.61	9.54	.52
FAGU013	6442	152.5	153.9	1.4	100	4C0	3.16	.06	1.35	1.36	15.0	.34	3.14	11.66		2.71	14.80	.50
FAGU013	6443	153.9	157.2	3.3	33	4A0	3.04	.03	.78	.81	9.0	.21	4.28	5.82		1.59	10.10	.51
FAGU013	6444	157.2	158.6	1.4	57	4EL4	3.58	.06	2.59	2.63	30.0	1.10	9.46	14.64		5.22	24.10	.50
FAGU013	6445	158.6	161.1	2.5	100	4G8#	4.34	.23	4.04	3.67	49.0	2.06	11.39	21.31		7.71	32.70	.48
FAGU013	6446	161.1	161.5	.4	100	4E47	4.29	.07	4.40	3.61	56.0	.89	10.93	24.37		8.01	35.30	.45
FAGU013	6447	178.0	179.8	1.8	100	4E8*	4.21	.22	1.56	.86	33.0	.75	9.92	24.58		2.42	34.50	.36
FAGU013	6448	179.8	181.3	1.5	100	4E8*	4.14	.15	2.66	.45	46.0	.75	11.11	21.79		3.11	32.90	.14
FAGU013	6449	181.3	182.9	1.6	100	4E8*	4.00	.20	1.36	.36	32.0	1.17	9.02	23.00		1.72	32.02	.21
FAGU020	6450	18.3	20.6	2.3	100	4G4	4.27	.21	7.87	13.80	150.0	.96	1.39	20.51		21.67	21.90	.64
FAGU020	6451	20.6	21.1	.5	100	5C4	3.16	.04	1.06	1.73	15.0	.96	1.87	10.33		2.79	12.20	.62
FAGU020	6452	21.1	23.0	1.9	95	4G4	4.30	.24	7.23	11.60	123.0	1.65	1.30	22.60		18.83	23.90	.62
FAGU020	6453	38.1	41.6	3.5	60	4A1		.11	.79	1.26	14.0					2.05		.61
FAGU020	6454	41.6	45.0	3.4	53	4A1		.07	.60	.95	17.0					1.55		.61
FAGU020	6455	45.0	47.2	2.2	77	4A1		.10	.82	.78	22.0					1.60		.49
FAGU020	6456	47.2	48.7	1.5	73	4A0		.06	.73	.88	19.0					1.61		.55
FAGU020	6457	59.4	60.3	.9	89	4D4		.09	5.34	7.13	88.0					12.47		.57
FAGU020	6458	71.3	72.8	1.5	100	4CDJ		.14	5.94	7.03	97.0					12.97		.54
FAGU027	6459	.0	1.5	1.5	20	4D5	3.91	.03	7.44	1.30	116.0	1.44	2.12	17.00		8.74	19.12	.15
FAGU027	6460	1.5	3.0	1.5	47	4A14	3.33	.10	3.62	6.61	61.0	1.10	1.78	12.20		10.23	13.98	.65
FAGU027	6461	3.0	4.7	1.7	71	4A13	3.75	.10	2.92	3.76	54.0	1.58	1.38	22.10		6.68	23.48	.56
FAGU027	6462	4.7	6.3	1.6	94	4A13	3.30	.07	2.74	1.86	54.0	1.44	1.20	14.20		4.60	15.40	.40
FAGU027	6463	6.3	7.7	1.4	100	4A13	3.75	.14	.69	.68	38.0	2.54	1.20	25.10		1.37	26.30	.50

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAO	PB+ZN	PC+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGU027	6464	7.7	9.0	1.3	69	4A13	3.94	.10	2.02	2.34	62.0	2.33	1.43	25.90		4.36	27.33	.54
FAGU027	6465	9.0	10.7	1.7	100	4A14	3.25	.03	1.97	4.80	47.0	.69	1.24	11.50		6.77	12.74	.71
FAGU027	6466	10.7	11.2	.5	80	4D0	2.91	.03	2.03	3.06	44.0	.62	.93	4.49		5.09	5.42	.60
FAGU027	6467	13.7	15.5	1.8	100	4A13	3.40	.05	.88	1.97	36.0	1.17	1.03	18.80		2.85	19.83	.69
FAGU027	6468	15.5	17.3	1.8	94	4A13	3.88	.07	3.10	4.90	52.0	1.58	2.49	24.00		8.00	26.49	.61
FAGU027	6469	17.3	19.1	1.8	72	4A13	3.36	.05	1.01	2.53	35.0	1.30	1.57	17.10		3.54	18.67	.71
FAGU027	6470	19.1	19.8	.7	100	4D0	3.52	.02	3.88	5.57	58.0	.82	1.67	16.27		9.45	17.94	.59
FAGU027	6471	21.1	22.0	.9	100	4E14	3.93	.06	7.05	5.32	98.0	1.51	1.40	21.50		12.37	22.90	.43
FAGU027	6472	22.5	23.1	.6	100	4E14	3.90	.04	7.28	8.02	122.0	1.30	1.69	18.40		15.30	20.09	.52
FAGU027	6473	24.2	25.8	1.6	44	4D0	3.33	.03	1.59	4.84	47.0	.55	2.88	14.30		6.43	17.18	.75
FAGU027	6474	25.8	27.4	1.6	62	4D0	3.39	.04	1.93	4.31	49.0	.69	1.55	15.40		6.24	16.95	.69
FAGU027	6475	29.1	30.2	1.1	55	4A1	3.05	.02	1.03	2.49	35.0	.82	1.05	9.10		3.52	10.15	.71
FAGU027	6476	30.2	31.5	1.3	100	4A34	3.56	.03	2.07	6.18	59.0	.89	1.75	16.70		8.25	18.45	.75
FAGU027	6477	31.5	33.3	1.8	83	4A14	3.73	.04	2.69	5.07	59.0	.69	1.08	11.00		7.76	12.08	.65
FAGU027	6478	33.3	35.1	1.8	89	4A14	3.20	.03	1.57	4.38	40.0	.41	.79	4.92		5.95	5.71	.74
FAGU027	6479	35.1	36.9	1.8	100	4A1	3.42	.02	1.22	2.35	37.0	.41	1.20	14.70		3.57	15.90	.66
FAGU027	6480	36.9	38.9	2.0	100	4A14	3.42	.05	1.92	3.79	52.0	.82	1.04	14.99		5.71	16.03	.66
FAGU027	6481	38.9	40.9	2.0	100	4A14	3.50	.07	1.72	6.22	53.0	.69	1.42	14.30		7.94	15.72	.78
FAGU027	6482	40.9	42.9	2.0	75	4A14	3.62	.04	4.10	6.76	84.0	.62	1.24	15.50		10.86	16.74	.62
FAGU027	6483	42.9	44.9	2.0	90	4A14	3.51	.13	1.40	4.06	45.0	1.10	1.20	18.70		5.46	19.90	.74
FAGU027	6484	44.9	46.9	2.0	100	4A1	3.20	.12	1.34	3.19	44.0	.75	1.07	11.90		4.53	12.97	.70
FAGU027	6485	46.9	48.9	2.0	100	4A1	3.21	.06	1.22	2.44	39.0	.89	.89	13.50		3.66	14.39	.67
FAGU027	6486	48.9	50.9	2.0	100	4A14	3.37	.07	3.30	6.77	55.0	.82	1.27	13.20		10.07	14.47	.67
FAGU027	6487	50.9	52.9	2.0	100	4A14	3.20	.05	2.40	5.95	43.0	.69	1.23	9.60		8.35	10.83	.71
FAGU027	6488	52.9	54.9	2.0	100	4A14	3.30	.05	4.03	7.26	67.0	1.99	1.20	10.90		11.29	12.10	.64
FAGU027	6489	54.9	56.9	2.0	100	4A14	3.31	.09	1.96	3.81	38.0	1.03	.94	15.10		5.77	16.04	.66
FAGU027	6490	56.9	58.9	2.0	100	4A1	3.47	.11	1.41	2.38	33.0	1.30	.64	14.18		3.79	14.82	.63
FAGU027	6491	58.9	60.9	2.0	95	4A1	3.21	.08	1.75	2.74	34.0	.89	1.08	12.70		4.49	13.78	.61
FAGU027	6492	60.9	62.4	1.5	93	4A14	3.14	.07	2.12	4.00	37.0	.69	1.12	9.70		6.12	10.82	.65
FAGU027	6493	62.4	63.9	1.5	100	4A14	3.18	.05	4.22	6.62	66.0	1.03	1.09	7.50		10.84	8.59	.61
FAGU027	6494	63.9	65.9	2.0	100	4A4	3.26	.05	5.14	10.40	88.0	.89	1.37	7.40		15.54	8.77	.67
FAGU027	6495	65.9	67.9	2.0	85	4A4	3.29	.04	3.49	8.61	62.0	.96	1.61	8.90		12.10	10.51	.71
FAGU027	6496	67.9	69.7	1.8	78	4AE4	3.41	.08	.46	5.30	13.0	.96	7.43	13.30		5.76	20.73	.92
FAGU027	6497	69.7	71.6	1.9	79	4A24	3.86	.06	7.69	14.10	133.0	1.23	1.71	8.80		21.79	10.51	.65
FAGU027	6498	71.6	73.5	1.9	79	4A24	3.49	.05	6.17	11.60	99.0	1.17	1.70	8.70		17.77	10.40	.65
FAGU027	6499	73.5	74.8	1.3	77	4D4	3.67	.11	3.59	7.61	66.0	.62	5.23	15.10		11.20	20.33	.68
FAGU027	6500	74.8	76.1	1.3	38	4D4	3.48	.05	4.40	8.93	71.0	.55	4.12	7.18		13.33	11.30	.67
FAGU086	6501	.0	2.4	2.4	63	4A12	3.41	.04	4.69	8.70	95.0	.82	1.93	12.30		13.39	14.23	.65
FAGU086	6502	2.4	3.3	.9	100	4A12	3.15	.04	1.50	4.23	47.0	.69	1.85	10.30		5.73	12.15	.74
FAGU086	6503	6.1	6.7	.6	100	4D4	3.75	.04	5.79	8.82	121.0	1.37	1.91	18.70		14.61	20.61	.60
FAGU086	6504	6.7	8.8	2.1	100	4E*4	4.09	.06	4.75	17.20	109.0	.89	5.39	17.70		21.95	23.09	.78
FAGU086	6505	8.8	9.9	1.1	100	4K4	3.68	.05	3.94	10.10	87.0	.48	5.86	14.00		14.04	19.86	.72
FAGU086	6506	54.6	55.6	1.0	70	4E#4		.13	5.21	9.36	113.0					14.57		.64
FAGU086	6507	81.2	82.6	1.4	100	4A14	3.03	.02	1.89	3.90	44.0	.41	2.40	4.18		5.79	6.58	.67
FAGU086	6508	82.6	84.0	1.4	100	4A14	3.04	.03	3.49	5.09	62.0	.69	1.55	4.78		8.58	6.33	.59
FAGU011	6510	.4	1.7	1.3	69	4D45	3.40	.06	3.67	9.42	76.0	1.10	1.50	13.20		13.09	14.70	.72
FAGU011	6511	1.7	3.0	1.3	54	4D45	3.28	.01	2.87	6.23	47.0	.82	1.36	12.14		9.10	13.50	.68
FAGU011	6512	5.3	6.7	1.4	100	4E*4	4.20	.06	3.98	17.60	83.0	.89	8.54	15.36		21.58	23.90	.82
FAGU011	6513	6.7	8.0	1.3	100	4E*4	4.48	.04	6.93	22.50	143.0	.82	8.28	15.02		29.43	23.30	.76
FAGU011	6514	8.0	9.3	1.3	92	4K4	4.03	.04	2.75	8.72	67.0	.41	4.23	20.67		11.47	24.90	.76

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAO	PB+ZN	PG+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGU084	6515	1.6	2.4	.8	100	4D5	3.52	.09	3.52	4.44	49.0	1.65	1.55	19.50		7.96	21.05	.56
FAGU084	6516	2.4	4.3	1.9	100	4A4	3.46	.03	4.80	7.07	74.0	1.37	1.60	16.20		11.87	17.80	.60
FAGU084	6517	4.3	6.3	2.0	100	4A4	3.25	.05	3.50	8.12	59.0	.96	2.12	11.60		11.62	13.72	.70
FAGU084	6518	10.2	11.8	1.6	88	4D4	3.59	.01	6.91	12.80	122.0	1.03	2.65	13.70		19.71	16.35	.65
FAGU084	6519	11.8	12.4	.6	100	4D#4	3.82	.07	7.69	11.90	146.0	2.26	2.15	18.10		19.59	20.25	.61
FAGU084	6520	13.1	14.1	1.0	100	4D*4	3.47	.12	6.56	12.40	129.0	2.13	2.56	11.50		18.96	14.06	.65
FAGU084	6521	14.1	15.5	1.4	100	4E4	4.06	.08	8.64	15.20	184.0	1.65	2.15	19.70		23.84	21.85	.64
FAGU084	6522	15.5	16.7	1.2	100	4E*4	3.63	.07	6.83	15.40	134.0	1.10	2.82	13.50		22.23	16.32	.69
FAGU084	6523	17.1	18.6	1.5	100	4K4	3.74	.10	3.13	7.84	84.0	1.58	3.13	21.00		10.97	24.13	.71
FAGU084	6524	37.6	38.1	.5	100	4A34		.04	2.54	2.54	42.0					5.08		.50
FAGU084	6525	41.2	43.3	2.1	100	4E12	4.19	.21	7.18	9.89	114.0	1.99	1.46	23.20		17.07	24.66	.58
FAGU084	6526	43.3	45.2	1.9	89	4D4	3.87	.04	6.61	17.50	103.0	1.17	1.42	17.70		24.11	19.12	.73
FAGU084	6527	45.2	47.1	1.9	32	4D4	3.77	.04	4.88	11.80	79.0	.89	1.65	17.70		16.68	19.35	.71
FAGU084	6528	47.1	47.9	.8	100	4G4	4.46	.05	4.03	9.05	70.0	.96	1.10	20.60		13.08	21.70	.69
FAGU084	6529	47.9	48.9	1.0	90	4E*4	4.69	.12	5.62	10.70	94.0	1.65	2.15	27.70		16.32	29.85	.66
FAGU084	6530	48.9	51.1	2.2	73	4G4	4.73	.12	4.38	6.99	84.0	1.44	.56	27.90		11.37	28.46	.61
FAGU084	6531	51.1	52.8	1.7	100	4E#4	4.67	.28	7.37	9.92	103.0	1.99	1.65	32.70		17.29	34.35	.57
FAGU084	6532	52.8	54.7	1.9	100	4G4	4.28	.14	5.39	9.63	99.0	1.58	1.05	23.10		15.02	24.15	.64
FAGA019	6533	135.9	137.8	1.9	95	4A13		.11	3.12	4.71	55.0					7.83		.60
FAGA019	6534	152.4	155.1	2.7	89	4A1	2.97	.09	1.46	2.50	23.0	.55	1.31	6.44		3.96	7.75	.63
FAGA019	6535	155.1	157.3	2.2	95	4A1	3.40	.07	.28	.39	8.0	.34	3.30	3.75		.67	7.05	.58
FAGA019	6536	157.3	158.5	1.2	100	4A1	3.16	.06	.16	.16	6.0	.27	4.00	5.40		.32	9.40	.50
FAGA019	6537	158.5	160.5	2.0	100	4A1	2.94	.04	1.26	1.62	14.0	.41	2.12	3.12		2.88	5.24	.56
FAGA019	6538	183.4	183.9	.5	100	4G#	4.35	.06	1.80	5.52	46.0	1.44	.95	20.80		7.32	21.75	.75
FAGA019	6539	205.3	207.6	2.3	35	4A31	3.61	.32	.38	1.09	17.0	.82	2.06	20.40		1.47	22.46	.74
FAGA019	6540	208.4	210.3	1.9	95	4C0	3.70	.25	.15	1.65	13.0	1.37	2.58	20.90		1.80	23.48	.92
FAGA019	6541	210.3	212.5	2.2	95	4C0	3.58	.25	.11	.62	13.0	.82	3.48	19.90		.73	23.38	.85
FAGA019	6542	212.5	214.6	2.1	100	4A13	3.35	.35	.05	.16	13.0	.41	2.05	17.75		.21	19.80	.76
FAGA019	6543	214.6	216.6	2.0	100	4A13	3.54	.35	.13	.13	10.0	.82	2.09	22.11		.26	24.20	.50
FAGA019	6544	216.6	218.8	2.2	100	4A14	3.50	.12	2.74	4.53	37.0	1.17	1.72	17.18		7.27	18.90	.62
FAGA019	6545	218.8	222.2	3.4	62	4A13	3.43	.31	.16	.71	12.0	.55	1.27	19.13		.87	20.40	.82
FAGA019	6546	222.2	224.9	2.7	44	4C0	3.43	.21	.09	4.02	12.0	.55	4.65	14.85		4.11	19.50	.98
FAGA019	6547	224.9	226.8	1.9	79	4C0	3.50	.38	.07	3.24	12.0	.55	3.50	18.80		3.31	22.30	.98
FAGA019	6548	226.8	229.5	2.7	56	4C0	3.69	.27	1.60	2.09	34.0	1.58	2.03	24.40		3.69	26.43	.57
FAGA129	6549	94.5	101.5	7.0	76	4AL1	3.02	.05	1.84	3.10	32.0	.48	2.21	5.70		4.94	7.91	.63
FAGA129	6550	101.5	105.6	4.1	100	4A43	3.23	.06	1.94	3.20	32.0	.69	1.65	12.80		5.14	14.45	.62
FAGU027	6551	78.7	79.8	1.1	100	4L4	3.34	.02	1.25	2.19	25.0	.34	4.60	3.79		3.44	8.39	.64
FAGU027	6552	84.3	85.3	1.0	100	4L12		.01	.49	1.08	13.0					1.57		.69
FAGU027	6553	92.8	94.7	1.9	100	4A4	3.37	.05	3.72	8.29	78.0	.41	1.06	11.20		12.01	12.26	.69
FAGU027	6554	96.0	97.1	1.1	55	4D4	4.01	.05	6.18	8.10	104.0	1.37	1.26	14.00		14.28	15.26	.57
FAGU027	6555	97.1	98.1	1.0	80	4A1	3.04	.05	2.31	4.35	40.0	.62	.94	11.00		6.66	11.94	.65
FAGU027	6556	98.1	99.1	1.0	20	4C0	3.70	.03	.81	1.31	20.0	.48	.75	22.30		2.12	23.05	.62
FAGU027	6557	103.5	103.9	.4	25	4L4	3.07	.02	1.47	4.37	26.0	.41	4.83	4.37		5.84	9.20	.75
FAGU027	6558	104.5	106.1	1.6	100	4A13	3.65	.07	6.45	10.30	110.0	1.17	1.96	16.20		16.75	18.16	.61
FAGU012	6559	15.8	17.4	1.6	94	4E4	4.49	.11	5.63	11.10	90.0	.55	2.58	25.82		16.73	28.40	.66
FAGU012	6560	17.4	19.1	1.7	94	4E4	4.50	.14	4.57	6.96	86.0	1.92	1.07	29.33		11.53	30.40	.60
FAGU012	6561	19.1	20.7	1.6	100	4E4	4.58	.15	5.52	7.54	100.0	1.51	.94	29.96		13.06	30.90	.58
FAGU012	6562	20.7	22.3	1.6	94	5C4*	3.19	.02	.60	3.37	21.0	.27	4.14	10.76		3.97	14.90	.85
FAGU012	6563	22.3	23.6	1.3	100	4E4	4.78	.15	4.49	6.53	84.0	.82	1.39	32.91		11.02	34.30	.59
FAGU012	6564	23.6	25.0	1.4	93	4E4	4.77	.20	5.41	10.50	95.0	1.65	1.83	28.07		15.91	29.90	.66

DDH	SAMPLE	---DEPTHS---		INT M	REC %	ROCK UNIT	S.G.	CU %	PB %	ZN %	AG G/MT	AU G/MT	PO %	PY %	BAO %	PB+ZN %	PO+PY %	ZN RATIO
		FROM	TO															
FAGU012	6565	25.0	26.2	1.2	100	4G4	4.63	.08	5.10	9.46	80.0	.96	.93	13.97		14.56	14.90	.65
FAGU012	6566	26.2	26.8	.6	83	4E4	4.70	.09	3.92	4.65	57.0	1.30	.66	33.24		8.57	33.90	.54
FAGU012	6567	26.8	27.3	.5	100	4G0	3.99	.01	1.36	3.70	23.0	.21	.95	14.45		5.06	15.40	.73
FAGU012	6568	27.3	28.8	1.5	100	4E4	4.42	.09	3.57	5.98	68.0	.75	.77	27.63		9.55	28.40	.63
FAGU012	6569	55.1	56.4	1.3	100	4D4	3.75	.51	6.59	5.70	133.0	2.40	5.89	15.11		12.29	21.00	.46
FAGU012	6570	56.4	57.6	1.2	100	4D4	3.80	.21	5.64	10.30	106.0	1.85	1.87	18.10		15.94	19.97	.65
FAGU012	6571	57.6	58.7	1.1	100	4E41	4.32	.15	6.01	10.90	90.0	1.99	1.36	24.84		16.91	26.20	.64
FAGU012	6572	58.7	59.9	1.2	100	4E41	4.14	.20	4.18	7.62	69.0	2.13	1.77	25.03		11.80	26.80	.65
FAGU012	6573	59.9	61.0	1.1	91	4C0	3.58	.35	.54	.81	16.0	1.65	2.43	22.00		1.35	24.43	.60
FAGU012	6574	61.0	62.5	1.5	87	4C5	4.50	.09	1.25	.91	31.0	1.78	1.43	18.97		2.16	20.40	.42
FAGU012	6575	62.5	63.9	1.4	86	4C5	4.03	.29	.12	.30	10.0	1.17	1.59	21.71		.42	23.30	.71
FAGU012	6576	63.9	65.5	1.6	63	4D0	3.16	.26	2.61	3.71	56.0	2.26	2.02	21.98		6.32	24.00	.59
FAGU012	6577	65.5	66.9	1.4	43	4D4	4.55	.13	5.15	6.36	78.0	1.65	1.70	17.90		11.51	19.60	.55
FAGU012	6578	66.9	70.1	3.2	37	4C0	3.92	.21	.48	1.35	18.0	.75	1.91	21.39		1.83	23.30	.74
FAGU012	6579	70.1	73.0	2.9	59	4C0	3.39	.18	.18	1.25	13.0	1.44	2.56	26.14		1.43	28.70	.87
FAGU012	6580	73.0	74.9	1.9	42	4C0	3.73	.19	1.57	2.29	41.0	1.13	1.67	23.43		3.86	25.10	.59
FAGU012	6581	74.9	75.9	1.0	50	4D*	3.49	.11	.27	7.78	12.0	1.30	8.14	14.66		8.05	22.80	.97
FAGU012	6582	75.9	77.7	1.8	100	4C0	3.25	.20	.36	2.40	20.0	.82	1.78	19.92		2.76	21.70	.87
FAGU012	6583	77.7	79.8	2.1	86	4C0	2.97	.21	.37	1.86	21.0	.34	1.62	18.08		2.23	19.70	.83
FAGA132	6584	70.6	72.8	2.2	100	4A13	3.52	.08	2.68	4.49	54.0	.82	1.39	14.41		7.17	15.80	.63
FAGA132	6585	72.8	75.1	2.3	96	4D0	4.52	.03	1.83	3.40	28.0	.27	2.65	7.35		5.23	10.00	.65
FAGA132	6586	75.1	77.1	2.0	100	4A4	3.56	.01	1.31	4.93	26.0	.34	.94	1.61		6.24	2.55	.79
FAGA132	6587	77.1	78.3	1.2	83	4A4	3.39	.03	2.98	6.56	49.0	.55	1.07	6.43		9.54	7.50	.69
FAGA132	6588	78.3	79.9	1.6	75	4A4	3.38	.03	3.67	6.96	59.0	.69	1.38	12.62		10.63	14.00	.65
FAGA132	6589	82.6	84.7	2.1	86	4EA	4.33	.06	1.46	2.09	32.0	.82	1.51	23.99		3.55	25.50	.59
FAGA132	6590	84.7	86.3	1.6	94	4EA	3.63	.06	1.99	2.58	44.0	1.10	1.28	22.80		4.57	24.08	.56
FAGA132	6591	86.3	88.1	1.8	100	4EA0	4.34	.05	1.32	1.94	33.0	.96	.99	27.91		3.26	28.90	.60
FAGA132	6592	88.1	90.8	2.7	59	5D4	3.32	.02	1.69	3.35	33.0	.21	5.86	6.34		5.04	12.20	.66
FAGA132	6593	94.5	96.2	1.7	88	4D45	2.86	.03	7.04	9.47	121.0	1.10	1.73	13.47		16.51	15.20	.57
FAGA132	6594	96.2	97.3	1.1	100	4A4	3.78	.06	6.35	11.80	110.0	1.03	1.36	8.49		18.15	9.85	.65
FAGA132	6595	97.3	98.5	1.2	100	4A4	3.84	.14	6.27	13.10	115.0	1.44	1.37	15.13		19.37	16.50	.68
FAGA132	6596	98.5	100.3	1.8	94	4A14	3.41	.05	2.61	6.68	53.0	.82	.97	10.33		9.29	11.30	.72
FAGA132	6597	100.3	102.7	2.4	96	4A14	3.59	.06	2.88	4.67	50.0	.89	.89	11.91		7.55	12.80	.62
FAGA132	6598	102.7	104.7	2.0	85	4A1	3.37	.06	1.67	3.03	41.0	.89	.76	10.44		4.70	11.20	.64
FAGA132	6599	104.7	106.2	1.5	100	4A1	3.45	.06	.91	2.47	25.0	.75	.75	10.55		3.38	11.30	.73
FAGA132	6600	106.2	108.3	2.1	100	4A1	3.36	.09	1.28	3.20	35.0	.89	.63	15.90		4.48	16.53	.71
FAGA129	6601	105.6	108.2	2.6	100	4CE4	3.70	.10	2.94	2.85	48.0	1.37	2.90	22.80		5.79	25.70	.49
FAGA129	6602	108.2	111.0	2.8	50	4CA3	3.47	.07	.72	1.93	17.0	.96	1.57	20.30		2.65	21.87	.73
FAGA129	6603	111.0	113.4	2.4	13	4D45	3.43	.05	6.64	13.90	115.0	.89	3.71	8.40		20.54	12.11	.68
FAGA129	6604	113.4	118.7	5.3	58	4AL3		.04	.21	.39	3.0					.60		.65
FAGU018	6605	14.3	16.0	1.7	88	4E4	4.56	.15	9.45	17.40	152.0	1.30	2.85	21.25		26.85	24.10	.65
FAGU018	6606	16.0	16.8	.8	63	4D45	4.31	.11	5.34	9.06	91.0	1.17	1.58	14.12		14.40	15.70	.63
FAGU018	6607	16.8	18.8	2.0	100	4E4	4.83	.11	11.70	15.80	142.0	1.78	3.51	24.49		27.50	28.00	.57
FAGU018	6608	18.8	20.7	1.9	100	4E4	4.80	.24	7.01	12.20	94.0	.96	3.54	25.56		19.21	29.10	.64
FAGU018	6609	20.7	22.9	2.2	95	4E4	4.74	.28	5.65	12.70	92.0	.96	3.86	25.34		18.35	29.20	.69
FAGU018	6610	22.9	24.1	1.2	100	4E4	4.61	.26	4.96	11.20	84.0	1.17	3.37	29.60		16.16	32.97	.69
FAGU018	6611	24.1	25.6	1.5	100	4E4	4.42	.17	4.24	6.86	88.0	3.02	1.45	26.35		11.10	27.80	.62
FAGU018	6612	25.6	26.1	.5	100	5C4\$	3.08	.02	.40	1.19	11.0	.21	1.69	8.31		1.59	10.00	.75
FAGU018	6613	26.1	27.5	1.4	100	4E0	4.00	.06	1.70	2.85	47.0	.62	1.42	28.58		4.55	30.00	.63
FAGU018	6614	27.5	29.6	2.1	90	4E51	3.91	.05	2.66	4.99	47.0	.62	1.09	21.31		7.65	22.40	.65

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAO	PB+ZN	PO+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGU018	6615	29.6	31.6	2.0	100	4E4	4.79	.32	4.68	11.20	70.0	.89	2.24	33.41		15.88	35.65	.71
FAGU018	6616	31.6	33.5	1.9	79	4E4	4.77	.27	8.03	17.10	115.0	1.51	1.85	26.18		25.13	28.03	.68
FAGU018	6617	33.5	35.6	2.1	81	4E4	4.63	.14	3.63	7.92	69.0	1.10	3.44	33.94		11.55	37.38	.69
FAGU018	6618	35.6	36.6	1.0	100	4E4	4.63	.14	2.80	5.95	65.0	.89	2.79	35.10		8.75	37.89	.68
FAGU018	6619	36.6	38.5	1.9	84	4E4	4.57	.18	4.13	7.43	80.0	.82	4.49	30.80		11.56	35.29	.64
FAGUC18	6620	51.8	53.3	1.5	100	4E46	4.07	.19	2.08	4.59	78.0	1.78	1.29	21.40		6.67	22.69	.69
FAGU018	6621	58.1	59.6	1.5	100	4G#	4.56	.01	1.95	5.46	42.0	.48	.39	13.20		7.41	13.59	.74
FAGU018	6622	59.6	61.0	1.4	86	4D0	3.76	.02	2.07	3.55	52.0	.69	.57	22.70		5.62	23.27	.63
FAGU018	6623	61.0	62.5	1.5	100	4A34	3.59	.02	1.79	3.68	38.0	.89	1.10	22.30		5.47	23.40	.67
FAGU018	6624	62.5	64.0	1.5	100	4D0	3.46	.08	1.91	5.01	49.0	.55	.77	14.60		6.92	15.37	.72
FAGU018	6625	64.0	65.5	1.5	100	4D0	3.43	.06	1.80	3.73	51.0	.27	.54	15.00		5.53	15.54	.67
FAGU018	6626	65.5	66.3	.8	100	4D4	3.70	.01	7.09	17.40	98.0	.75	1.62	8.40		24.49	10.02	.71
FAGU018	6627	66.3	67.6	1.3	100	4D0	3.66	.04	2.04	5.72	49.0	.48	.66	17.80		7.76	18.46	.74
FAGU018	6628	67.6	69.3	1.7	100	4G4*	4.07	.03	4.50	10.90	76.0	.82	1.04	15.50		15.40	16.54	.71
FAGU018	6629	69.3	70.2	.9	100	4G*	3.53	.04	3.00	6.77	68.0	.55	.69	16.20		9.77	16.89	.69
FAGU018	6630	70.2	72.4	2.2	100	4G4*	3.82	.05	3.81	9.50	69.0	.82	.71	17.10		13.31	17.81	.71
FAGU018	6631	72.4	74.7	2.3	96	4E4	4.70	.24	3.84	5.82	63.0	2.19	1.16	35.20		9.66	36.36	.60
FAGU018	6632	74.7	76.8	2.1	100	4E0	4.61	.11	1.33	2.47	39.0	1.44	1.02	37.60		3.80	38.62	.65
FAGU018	6633	76.8	79.2	2.4	100	4E4	4.65	.18	3.70	6.29	77.0	1.92	1.04	35.10		9.99	36.14	.63
FAGU018	6634	79.2	79.9	.7	86	4A4	3.41	.02	6.28	11.50	105.0	1.03	1.19	9.10		17.78	10.29	.65
FAGU018	6635	80.4	82.3	1.9	100	4A1		.07	.46	.88	16.0					1.34		.66
FAGU018	6636	82.3	84.2	1.9	100	4A1		.08	.72	.99	19.0					1.71		.58
FAGU018	6637	84.2	86.3	2.1	100	4A1		.10	.07	.14	20.0					.21		.67
FAGU018	6638	86.3	88.4	2.1	100	4A1		.08	.10	.27	18.0					.37		.73
FAGU016	6639	43.2	43.8	.6	100	4A1		.04	.60	2.58	13.0					3.18		.81
FAGUC16	6640	58.9	59.9	1.0	100	4A0		.14	.24	.44	15.0					.68		.65
FAGU016	6641	59.9	60.3	.4	100	4H4	4.04	.08	9.57	18.60	122.0	.48	12.80	7.30		28.17	20.10	.66
FAGU016	6642	61.1	63.0	1.9	100	4E*4	4.48	.11	6.81	12.60	116.0	1.71	1.27	27.70		19.41	28.97	.65
FAGU016	6643	63.0	63.9	.9	100	4G4	4.39	.15	6.40	14.40	128.0	1.51	.93	25.00		20.80	25.93	.69
FAGU016	6644	63.9	65.1	1.2	100	4K4	4.16	.05	2.47	8.75	54.0	1.03	1.98	26.60		11.22	28.58	.78
FAGU016	6645	65.1	66.3	1.2	58	4KD	4.19	.06	1.46	5.08	52.0	.75	1.67	28.90		6.54	30.57	.78
FAGU016	6646	66.3	66.7	.4	100	4A34	3.63	.07	4.49	10.20	65.0	1.17	1.15	16.40		14.69	17.55	.69
FAGU016	6647	66.7	68.7	2.0	100	4A13	3.21	.10	.63	1.00	18.0	.75	.85	15.00		1.63	15.85	.61
FAGUC09	6648	2.3	3.2	.9	89	4D0	3.55	.11	1.03	4.11	23.0	.69	3.88	16.50		5.14	20.38	.80
FAGUC09	6649	4.5	6.1	1.6	100	4A14	3.32	.03	3.14	3.50	48.0	.89	.96	12.50		6.64	13.46	.53
FAGU009	6650	6.1	7.7	1.6	100	4A14	3.60	.07	1.71	3.93	37.0	1.37	2.36	20.60		5.64	22.96	.70
FAGA132	6651	108.3	110.8	2.5	92	4A1	3.01	.03	.99	2.40	22.0	.48	1.61	6.39		3.39	8.00	.71
FAGA132	6652	110.8	112.0	1.2	100	4A1	3.61	.02	1.21	2.73	28.0	.48	1.21	12.00		3.94	13.21	.69
FAGA132	6653	112.0	113.9	1.9	100	4A1	3.27	.01	1.43	4.27	38.0	.62	.87	12.40		5.70	13.27	.75
FAGA132	6654	113.9	116.0	2.1	90	4A14	3.34	.01	1.29	3.93	37.0	.69	.98	16.10		5.22	17.08	.75
FAGA132	6655	116.0	117.2	1.2	100	4A1	3.68	.02	1.15	3.44	36.0	.96	1.36	22.50		4.59	23.86	.75
FAGA132	6656	117.2	118.9	1.7	88	4A14	3.24	.02	1.80	5.21	44.0	.55	.81	8.80		7.01	9.61	.74
FAGA132	6657	118.9	120.2	1.3	100	4A14	3.40	.01	2.09	4.75	52.0	.69	.75	.25		6.84	1.00	.69
FAGA132	6658	134.9	135.6	.7	86	4G#	4.80	.01	.80	2.70	30.0	.48	.90	32.10		3.50	33.00	.77
FAGA132	6659	135.6	136.3	.7	86	4A4	3.78	.01	9.92	1.77	168.0	.69	2.19	14.10		11.69	16.29	.15
FAGA132	6660	136.3	137.6	1.3	100	4D#	3.70	.04	6.66	1.31	89.0	.27	1.68	12.89		7.97	14.57	.16
FAGA132	6661	137.6	139.2	1.6	100	4A4	3.99	.04	5.95	1.47	120.0	.82	1.50	10.50		7.42	12.00	.20
FAGA132	6662	139.2	140.5	1.3	92	4L0	3.16	.01	.39	1.05	9.0	.21	.93	8.50		1.44	9.43	.73
FAGA132	6663	140.5	142.3	1.8	83	4A4	3.39	.01	2.40	5.70	47.0	.41	1.08	11.00		8.10	12.08	.70
FAGA162	6664	62.3	63.2	.9	100	4EL	3.81	.27	1.09	1.10	20.0	.21	10.90	13.20		2.19	24.10	.50

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAG	PB+ZN	PO+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGA162	6665	63.2	65.0	1.8	89	4EL	3.86	.16	2.60	2.60	33.0	.69	6.51	21.70		5.20	28.21	.50
FAGA162	6666	65.0	66.4	1.4	100	4E0	4.84	.10	3.40	1.60	45.0	1.51	4.66	32.38		5.00	37.04	.32
FAGA162	6667	66.4	67.5	1.1	91	4CL9		.24	.27	.49	19.0					.76		.64
FAGA162	6668	67.5	69.2	1.7	100	4C35		.11	.16	.25	8.0					.41		.61
FAGA162	6669	69.2	70.9	1.7	100	4C35		.10	.08	.21	9.0					.29		.72
FAGA162	6670	70.9	72.0	1.1	100	4C3		.30	.10	.22	20.0					.32		.69
FAGA162	6671	72.0	74.5	2.5	96	4C35		.19	.11	.21	14.0					.32		.66
FAGA162	6672	74.5	76.9	2.4	92	4C35		.13	.14	.29	11.0					.43		.67
FAGA162	6673	76.9	78.0	1.1	100	4C*L		.13	.18	.26	11.0					.44		.59
FAGA162	6674	78.0	80.5	2.5	88	4E#	4.42	.12	2.09	1.08	51.0	.96	5.29	31.60		3.17	36.89	.34
FAGA162	6675	80.5	82.0	1.5	100	4AC3	3.35	.17	.17	.26	12.0	.69	2.01	18.00		.43	20.01	.60
FAGA162	6676	82.0	83.5	1.5	100	4C*L	3.70	.21	.47	1.69	18.0	.55	4.46	18.80		2.16	23.26	.78
FAGA162	6677	83.5	84.8	1.3	92	4GE*4	4.56	.21	6.50	7.80	100.0	1.44	3.21	25.40		14.30	28.61	.55
FAGA024	6678	178.9	180.1	1.2	100	4A41	3.42	.11	4.10	5.20	75.0	1.44	1.07	15.40		9.30	16.47	.56
FAGA024	6679	204.2	206.3	2.1	100	4A1		.12	.70	.40	19.0					1.10		.36
FAGA024	6680	206.3	208.1	1.8	100	4A1		.14	.65	.41	18.0					1.06		.39
FAGA024	6681	208.1	208.8	.7	100	5C4		.02	.17	.41	8.0					.58		.71
FAGA024	6682	208.8	209.6	.8	75	4A1	3.38	.06	1.42	1.90	29.0	.62	2.09	13.10		3.32	15.19	.57
FAGA024	6683	209.6	210.9	1.3	100	5C4	3.04	.03	.24	.39	9.0	.07	3.96	4.37		.63	8.33	.62
FAGA024	6684	210.9	213.2	2.3	96	4A1	3.03	.08	.29	.51	9.0	.89	.97	9.10		.80	10.07	.64
FAGA024	6685	213.2	214.9	1.7	100	4A1	3.19	.10	1.51	3.20	27.0	1.78	.80	10.60		4.71	11.40	.68
FAGA024	6686	214.9	216.9	2.0	100	4A1	3.25	.07	1.19	2.10	18.0	1.30	.52	13.10		3.29	13.62	.64
FAGA024	6687	216.9	218.5	1.6	100	4A14	3.29	.02	2.60	5.00	33.0	.75	.91	13.60		7.60	14.51	.66
FAGA024	6688	251.8	253.5	1.7	94	4G4	4.72	.07	4.60	8.70	77.0	1.65	.68	18.80		13.30	19.48	.65
FAGA024	6689	328.6	329.2	.6	100	4D4	3.72	.02	9.50	15.70	125.0	1.85	4.87	5.12		25.20	9.99	.62
FAGA024	6690	329.2	329.8	.6	100	4G0	4.45	.03	2.70	6.00	46.0	.82	.63	15.10		8.70	15.73	.69
FAGA024	6691	329.8	330.5	.7	100	4D0	3.75	.06	3.20	6.70	63.0	.89	.27	11.90		9.90	12.17	.68
FAGA024	6692	330.5	332.4	1.9	100	4B4	3.82	.05	6.70	15.80	112.0	1.23	1.52	11.70		22.50	13.22	.70
FAGA024	6693	332.4	334.6	2.2	91	4E4	4.73	.27	4.60	7.00	75.0	1.92	1.10	33.00		11.60	34.10	.60
FAGA024	6694	334.6	337.0	2.4	83	4E4	4.80	.27	5.80	7.90	91.0	1.37	1.25	29.60		13.70	30.85	.58
FAGA024	6695	337.0	337.9	.9	100	4D4	3.68	.12	5.60	13.80	111.0	1.44	1.59	12.70		19.40	14.29	.71
FAGA024	6696	337.9	338.9	1.0	100	4E4	4.83	.29	6.00	8.80	100.0	1.92	1.40	32.40		14.80	33.80	.59
FAGA024	6697	338.9	340.1	1.2	100	4A14	3.61	.07	4.80	9.60	73.0	1.23	1.69	13.30		14.40	14.99	.67
FAGA024	6698	340.1	341.4	1.3	92	4A14	3.55	.03	4.70	9.10	68.0	1.17	1.98	10.50		13.80	12.48	.66
FAGA024	6699	341.4	342.6	1.2	100	4E4	4.29	.22	5.60	7.80	86.0	2.19	1.54	27.90		13.40	29.44	.58
FAGA024	6700	342.6	343.0	.4	75	4A41	4.02	.08	6.30	14.80	132.0	1.23	1.76	13.70		21.10	15.46	.70
FAGU009	6701	7.7	9.4	1.7	100	4A14	3.79	.06	4.67	3.55	54.0	1.51	1.36	20.20		8.22	21.56	.43
FAGU009	6702	9.4	11.5	2.1	81	4A14	3.82	.05	5.64	3.44	59.0	1.78	1.65	18.20		9.08	19.85	.38
FAGU009	6703	11.5	13.6	2.1	81	4A14	3.61	.03	3.34	6.84	44.0	1.03	2.41	15.70		10.18	18.11	.67
FAGU009	6704	13.6	15.6	2.0	100	4A14	3.87	.09	3.79	5.44	55.0	1.92	1.84	22.10		9.23	23.94	.59
FAGU009	6705	15.6	16.8	1.2	100	4A4	3.16	.02	2.09	3.99	37.0	.96	1.43	8.30		6.08	9.73	.66
FAGU009	6706	16.8	18.0	1.2	100	4A4	3.25	.01	3.21	7.04	52.0	.82	1.32	8.10		10.25	9.42	.69
FAGU009	6707	18.9	19.5	.6	100	4L14	3.14	.01	1.72	4.31	26.0	.55	1.58	7.80		6.03	9.38	.71
FAGU009	6708	22.3	23.7	1.4	100	4A1	3.01	.01	.74	2.75	18.0	.41	1.31	6.30		3.49	7.61	.79
FAGU009	6709	23.7	25.0	1.3	100	4A14	3.25	.02	4.17	9.58	71.0	.82	1.83	6.80		13.75	8.63	.70
FAGU009	6710	25.0	25.6	.6	100	4E14	3.94	.10	7.36	17.30	119.0	1.51	1.18	15.14		24.66	16.32	.70
FAGU009	6711	25.6	27.1	1.5	100	4A14	3.74	.07	9.20	12.30	126.0	1.65	2.11	13.70		21.50	15.81	.57
FAGU009	6712	29.0	29.7	.7	100	4A14	3.61	.07	5.50	7.00	116.0	1.78	1.42	15.30		12.50	16.72	.56
FAGU009	6713	29.7	31.0	1.3	92	4E1*	4.11	.24	7.20	16.70	207.0	1.99	2.81	16.20		23.90	19.01	.70
FAGU009	6714	35.2	36.7	1.5	93	4A34	3.45	.07	3.20	5.60	44.0	2.19	2.55	13.40		8.80	15.95	.64

DDH	SAMPLE	---DEPTHS---		INT M	REC %	ROCK UNIT	S.G.	CU %	PB %	ZN %	AG G/MT	AU G/MT	PC %	PY %	BAO %	PB+ZN %	PC+PY %	ZN RATIO
		FROM	TO															
FAGUC09	6715	39.5	40.2	.7	100	4D4	3.68	.12	4.10	6.90	73.0	1.37	1.98	17.00		11.00	18.98	.63
FAGUC09	6716	40.2	41.7	1.5	67	4E14	4.03	.03	7.90	12.90	115.0	1.71	1.98	18.80		20.80	20.78	.62
FAGUC09	6717	41.7	42.5	.8	100	4E64	4.55	.06	6.70	11.90	120.0	1.71	1.43	22.60		18.60	24.03	.64
FAGUC09	6718	42.5	44.0	1.5	47	4D4	3.93	.03	8.40	11.90	161.0	1.65	1.45	17.60		20.30	19.05	.59
FAGUC09	6719	44.0	45.5	1.5	100	4D4	3.94	.08	4.60	9.10	93.0	1.23	.83	21.70		13.70	22.53	.66
FAGUC09	6720	45.5	47.4	1.9	26	4E4	3.17	.15	4.80	8.10	101.0	1.44	1.40	31.10		12.90	32.50	.63
FAGUC09	6721	47.4	49.3	1.9	100	4E4	4.69	.17	5.40	8.10	67.0	1.78	1.21	33.10		13.50	34.31	.60
FAGUC09	6722	49.3	51.2	1.9	100	4E4	4.75	.20	6.00	8.90	90.0	1.85	1.19	31.40		14.90	32.59	.60
FAGUC09	6723	51.2	53.3	2.1	95	4A14	3.74	.05	1.87	3.80	28.0	2.06	2.53	17.50		5.67	20.03	.67
FAGUC07	6724	11.2	14.0	2.8	82	4L14	3.16	.10	4.00	2.10	43.0	1.44	.95	9.80		6.10	10.75	.34
FAGUC07	6725	14.0	15.2	1.2	100	4A14	3.05	.07	3.30	2.80	37.0	.89	1.10	6.00		6.10	7.10	.46
FAGUC07	6726	23.0	25.1	2.1	100	4A14	3.02	.05	2.30	3.50	36.0	1.23	1.35	5.10		5.80	6.45	.60
FAGUC23	6727	8.8	10.2	1.4	100	4A0	2.89	.01	1.74	2.90	23.0	.48	1.10	1.14		4.64	2.24	.63
FAGUC23	6728	10.2	11.6	1.4	100	4A0	2.86	.02	1.20	2.40	14.0	.48	.86	.78		3.60	1.64	.67
FAGUC23	6729	19.2	20.5	1.3	100	4A1		.03	.92	2.50	11.0					3.42		.73
FAGUC23	6730	20.5	22.3	1.8	94	4A1		.03	1.39	.49	21.0					1.88		.26
FAGUC23	6731	31.8	33.9	2.1	90	4E4	4.49	.14	3.30	4.90	68.0	1.23	2.26	38.60		8.20	40.86	.60
FAGUC23	6732	33.9	35.7	1.8	94	4E4	4.74	.14	3.20	5.80	63.0	1.30	1.72	36.20		9.00	37.92	.64
FAGUC23	6733	35.7	37.7	2.0	80	4E4	4.80	.17	4.80	9.40	104.0	1.58	3.72	29.50		14.20	33.22	.66
FAGUC23	6734	37.7	39.9	2.2	77	4E4	4.57	.09	4.70	8.60	93.0	1.23	1.49	23.20		13.30	24.69	.65
FAGUC23	6735	39.9	41.6	1.7	88	4E0	4.69	.03	1.43	3.40	32.0	.89	1.92	39.00		4.83	40.92	.70
FAGUC23	6736	41.6	43.8	2.2	77	4E4	4.51	.19	4.30	6.60	80.0	1.17	3.05	30.90		10.90	33.95	.61
FAGUC23	6737	43.8	45.7	1.9	79	4E4	4.74	.34	3.30	4.40	85.0	1.65	2.66	36.60		7.70	39.26	.57
FAGUC23	6738	45.7	48.8	3.1	58	4E4	4.73	.29	2.40	3.40	55.0	1.30	2.45	36.40		5.80	38.85	.59
FAGUC23	6739	48.8	50.6	1.8	100	4E4	4.75	.20	2.60	4.00	53.0	1.65	1.69	39.10		6.60	40.79	.61
FAGUC23	6740	50.6	52.5	1.9	100	4E0	4.69	.23	.89	1.34	23.0	1.58	1.29	39.88		2.23	41.17	.60
FAGUC23	6741	52.5	54.9	2.4	100	4E0	4.57	.25	1.23	1.57	30.0	1.78	1.51	38.00		2.80	39.51	.56
FAGUC23	6742	54.9	56.6	1.7	100	4E4	4.56	.27	2.25	2.80	63.0	1.71	1.81	35.40		5.05	37.21	.55
FAGUC23	6743	56.6	56.9	.3	100	4D45	3.88	.08	7.50	13.50	143.0	1.51	1.37	15.40		21.00	16.77	.64
FAGUC23	6744	56.9	58.7	1.8	100	4A1	3.20	.11	.82	1.31	20.0	.75	.88	13.20		2.13	14.08	.62
FAGUC23	6745	58.7	60.7	2.0	100	4A1	3.07	.07	.33	.44	10.0	.48	.69	10.70		.77	11.39	.57
FAGUC23	6746	62.6	64.0	1.4	100	4A1	3.09	.07	.41	.50	10.0	.55	.63	11.20		.91	11.83	.55
FAGUC23	6747	64.0	65.5	1.5	100	4A1	3.13	.09	1.18	1.32	21.0	.69	.97	12.50		2.50	13.47	.53
FAGUC23	6748	65.5	67.1	1.6	100	4A1	3.19	.13	.08	.21	16.0	.55	.98	15.20		.29	16.18	.72
FAGUC23	6749	67.8	69.2	1.4	100	4A4	3.51	.05	5.80	10.40	100.0	1.23	1.43	11.10		16.20	12.53	.64
FAGUC23	6750	69.2	70.1	.9	100	4A1	3.45	.18	.66	1.08	29.0	.75	.81	16.93		1.74	17.74	.62
FAGUC24	6751	343.0	343.6	.6	83	4D4	3.79	.08	6.30	14.30	120.0	1.78	1.74	9.60		20.60	11.34	.69
FAGUC17	6752	35.8	36.6	.8	100	4A1	3.27	.10	1.65	2.80	39.0	.89	1.12	14.10		4.45	15.22	.63
FAGUC17	6753	36.6	38.3	1.7	82	4E4	4.65	.09	3.60	7.40	85.0	.82	.91	34.90		11.00	35.81	.67
FAGUC17	6754	38.3	39.8	1.5	93	4E4	4.66	.06	2.80	4.50	57.0	.89	.86	38.50		7.30	39.36	.62
FAGUC17	6755	39.8	41.1	1.3	100	4E46	4.76	.11	3.40	5.40	67.0	.62	.77	37.30		8.80	38.07	.61
FAGUC17	6756	41.1	42.3	1.2	100	4E46	4.58	.16	7.00	13.20	130.0	1.10	.71	27.40		20.20	28.11	.65
FAGUC17	6757	42.3	43.3	1.0	100	4D45	3.36	.15	4.00	7.20	76.0	.82	1.23	11.30		11.20	12.53	.64
FAGUC17	6758	43.3	44.1	.8	88	4G4	4.46	.06	4.00	7.60	91.0	.89	.75	30.70		11.60	31.45	.66
FAGUC17	6759	44.1	44.6	.5	100	4K0	3.84	.04	.64	.98	40.0	.48	1.80	26.40		1.62	28.20	.60
FAGUC17	6760	44.6	45.0	.4	100	4E46	4.44	.11	4.90	10.40	98.0	.96	.81	27.80		15.30	28.61	.68
FAGUC17	6761	45.0	45.5	.5	80	4K4	4.20	.02	2.40	6.20	51.0	.62	.88	29.50		8.60	30.38	.72
FAGUC17	6762	45.5	46.3	.8	75	4E6#	4.35	.05	4.10	8.10	87.0	.75	1.46	26.60		12.20	28.06	.66
FAGUC17	6763	46.3	47.3	1.0	100	4G4	4.80	.14	3.40	6.80	96.0	1.03	.48	20.20		10.20	20.68	.67
FAGUC17	6764	47.3	48.5	1.2	83	4E4	4.87	.21	4.40	4.80	71.0	1.37	.95	36.30		9.20	37.25	.52

DDH	SAMPLE	---DEPTHS---		INT M	REC %	ROCK UNIT	S.G.	CU %	PB %	ZN %	AG G/MT	AU G/MT	PO %	PY %	BAO %	PB+ZN %	PC+PY %	ZN RATIO
		FROM	TO															
FAGU017	6765	48.5	50.9	2.4	100	4G4	4.61	.14	7.40	14.00	131.0	1.51	.94	23.90		21.40	24.84	.65
FAGU017	6766	50.9	52.9	2.0	100	4A0	3.31	.10	1.47	2.40	35.0	.82	1.00	13.50		3.87	14.50	.62
FAGU017	6767	52.9	54.9	2.0	100	4A4	3.44	.11	2.80	4.00	50.0	1.03	.94	11.60		6.80	12.54	.59
FAGU017	6768	54.9	56.5	1.6	13	4A0	3.17	.11	.61	1.20	18.0	.75	.61	9.90		1.81	10.51	.66
FAGU017	6769	68.2	69.8	1.6	94	4A1		.06	.69	1.27	15.0					1.96		.65
FAGU017	6770	69.8	71.3	1.5	100	4A1		.06	.95	1.52	19.0					2.47		.62
FAGU017	6771	73.4	74.7	1.3	100	4L12		.06	.51	.95	12.0					1.46		.65
FAGU017	6772	81.7	83.4	1.7	94	4A1		.07	.08	.11	8.0					.19		.58
FAGU017	6773	93.7	95.4	1.7	88	4A1		.12	.13	.51	7.0					.64		.80
FAGU017	6774	102.4	103.6	1.2	92	4A1		.24	.07	.27	13.0					.34		.79
FAGU017	6775	108.0	108.5	.5	100	4E1		.51	.07	1.13	15.0					1.20		.94
FAGU017	6776	108.5	110.4	1.9	84	4A1		.08	.07	.51	9.0					.58		.88
FAGU017	6777	114.0	116.1	2.1	100	4E1	4.55	.22	1.34	1.58	35.0	1.71	7.64	30.30		2.92	37.94	.54
FAGU017	6778	117.7	118.3	.6	100	4D45	3.92	.07	5.70	11.50	91.0	2.06	1.94	17.50		17.20	19.44	.67
FAGU017	6779	118.3	118.7	.4	100	4A41	3.39	.07	3.30	5.90	47.0	1.44	2.96	10.60		9.20	13.56	.64
FAGU017	6780	118.7	119.2	.5	100	4L0	2.96	.02	.12	.57	6.0	.27	4.47	2.46		.69	6.93	.83
FAGU017	6781	119.2	119.9	.7	100	4D4	3.49	.05	3.40	7.60	52.0	.89	4.04	9.00		11.00	13.04	.69
FAGA083	6782	144.3	145.1	.8	100	4C0	3.25	.14	1.21	1.50	19.0	.14	9.10	5.80		2.71	14.90	.55
FAGA083	6783	192.3	192.6	.3	100	5B69	2.97	.05	1.70	3.60	29.0	.55	3.19	1.31		5.30	4.50	.68
FAGA083	6784	192.6	193.6	1.0	90	4D0	3.52	.19	2.15	2.90	39.0	1.03	2.30	17.20		5.05	19.50	.57
FAGA083	6785	193.6	194.0	.4	100	4E4	4.52	.21	3.50	4.20	51.0	.75	2.50	30.90		7.70	33.40	.55
FAGA083	6786	194.0	194.5	.5	100	4C0	3.56	.20	1.10	.95	18.0	.89	9.10	11.30		2.05	20.40	.46
FAGA083	6787	194.5	195.9	1.4	100	4A13	3.39	.15	.15	.20	10.0	.41	3.17	12.50		.35	15.67	.57
FAGA083	6788	195.9	197.3	1.4	100	4A13	3.38	.16	.48	.25	13.0	.34	2.30	12.50		.73	14.80	.34
FAGA083	6789	197.3	197.8	.5	100	4E1@	4.33	.14	1.49	1.47	20.0	.21	3.34	16.60		2.96	19.94	.50
FAGA083	6790	222.2	223.8	1.6	100	4E#8		.17	1.00	.92	25.0					1.92		.48
FAGA083	6791	223.8	225.9	2.1	100	4A1		.08	.20	.10	10.0					.30		.33
FAGA083	6792	238.4	240.4	2.0	100	4A1		.14	.07	.29	6.0					.36		.81
FAGA083	6793	254.5	255.8	1.3	100	4E0		.01	.10	.05	6.0					.15		.33
FAGA083	6794	255.8	257.1	1.3	100	4E0		.02	.14	.18	8.0					.32		.56
FAGA083	6795	258.6	260.0	1.4	100	4E15		.08	1.13	.14	26.0					1.27		.11
FAGA083	6796	260.0	261.5	1.5	93	4A0	3.54	.11	1.73	1.90	34.0	.27	11.30	9.20		3.63	20.50	.52
FAGA083	6797	261.5	263.3	1.8	94	4A0	3.48	.05	1.10	1.44	23.0	.21	8.40	9.70		2.54	18.10	.57
FAGA083	6798	273.5	274.0	.5	100	4A0		.03	1.07	.10	20.0					1.17		.09
FAGU083	6799	5.7	7.6	1.9	79	4A41	3.15	.03	3.51	7.10	65.0	.69	4.17	4.78		10.61	8.95	.67
FAGU083	6800	7.6	8.3	.7	100	4A10	3.12	.10	1.30	3.00	25.0	.82	3.97	10.40		4.30	14.37	.70
FAGU022	6801	.0	.4	.4	100	4C0	3.03	.10	1.41	2.02	21.0	.41	1.80	6.20		3.43	8.00	.59
FAGU022	6802	.4	3.0	2.6	62	4A1	3.14	.08	1.95	.37	34.0	.82	1.82	8.40		2.32	10.22	.16
FAGU022	6803	4.6	5.5	.9	100	4A1	3.17	.14	1.76	.39	32.0	.82	1.55	9.10		2.15	10.65	.18
FAGU022	6804	5.5	7.2	1.7	100	4C0	2.98	.06	1.49	1.67	20.0	.48	1.43	5.60		3.16	7.03	.53
FAGU022	6805	7.2	9.1	1.9	100	4A1	2.99	.07	1.91	1.81	29.0	.48	.99	5.20		3.72	6.19	.49
FAGU022	6806	9.1	10.7	1.6	100	4A1	2.94	.03	1.99	1.17	24.0	.62	1.03	3.75		3.16	4.78	.37
FAGU022	6807	12.2	14.0	1.8	100	4A1	3.01	.06	2.20	.59	24.0	.32	.77	6.10		2.79	6.87	.21
FAGU022	6808	14.0	16.2	2.2	100	4A1	3.71	.07	.40	.24	9.0	.55	1.03	7.60		.64	8.63	.38
FAGU022	6809	16.2	18.2	2.0	100	4A1	3.20	.09	.63	.82	15.0	.62	1.42	10.70		1.45	12.12	.57
FAGU022	6810	18.2	19.8	1.6	100	4A1	3.16	.12	1.23	1.76	21.0	.89	.65	6.53		2.99	7.18	.59
FAGU022	6811	19.8	21.3	1.5	100	4A1	3.05	.04	2.30	1.87	33.0	.75	.79	6.10		4.17	6.89	.45
FAGU022	6812	22.9	24.5	1.6	100	4A14	3.44	.09	3.80	5.50	59.0	.69	1.23	13.30		9.30	14.53	.59
FAGU022	6813	24.5	26.3	1.8	100	4A1	3.55	.15	1.98	2.70	35.0	.89	1.46	18.10		4.68	19.56	.58
FAGU022	6814	26.3	26.8	.5	100	4E14	4.18	.31	2.20	4.40	49.0	.75	2.11	29.00		6.60	31.11	.67

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAO	PB+ZN	PO+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	%
FAGU022	6815	26.8	27.5	.7	71	4045	3.98	.08	9.70	11.00	132.0	.82	1.86	16.70		20.70	16.50	.55
FAGU022	6816	27.5	28.9	1.4	100	4E4	3.59	.08	10.70	15.10	220.0	2.19	2.54	23.20		25.80	25.74	.57
FAGU022	6817	28.9	32.0	3.1	100	4E4	4.52	.21	7.90	15.20	127.0	1.17	1.80	23.30		23.10	25.10	.60
FAGU022	6818	32.0	34.2	2.2	86	4E4	4.66	.15	6.10	11.00	101.0	.96	2.55	27.40		17.10	29.95	.64
FAGU022	6819	34.2	35.7	1.5	53	5C43	4.00	.12	2.50	4.90	40.0	.96	2.27	23.30		7.40	25.57	.66
FAGU022	6820	35.7	37.0	1.3	100	5C43	3.93	.06	1.55	2.30	27.0	.69	1.94	22.84		3.85	24.78	.60
FAGU022	6821	37.0	39.1	2.1	95	4E4	4.65	.15	3.90	8.50	71.0	1.03	4.41	28.90		12.40	33.31	.69
FAGU022	6822	39.1	41.0	1.9	100	4E4	4.50	.17	4.80	8.00	89.0	1.30	2.84	26.90		12.80	29.74	.63
FAGU022	6823	63.8	65.8	2.0	95	4D4	3.94	.38	7.90	6.40	123.0	2.40	2.41	15.70		14.30	18.11	.45
FAGU022	6824	65.8	67.8	2.0	100	4D4	4.04	.44	7.20	12.00	129.0	2.26	3.16	17.70		19.20	20.86	.63
FAGU022	6825	67.8	69.8	2.0	100	4D4	3.72	.32	4.10	6.10	73.0	1.85	3.51	16.90		10.20	20.41	.60
FAGU022	6826	69.8	71.3	1.5	100	4D4	3.73	.20	8.30	9.10	116.0	2.40	4.56	12.60		17.40	17.16	.52
FAGU022	6827	71.3	72.4	1.1	100	4D4	3.79	.14	6.60	7.20	110.0	1.78	3.86	15.90		13.80	19.76	.52
FAGU022	6828	72.4	73.4	1.0	100	4L0	3.00	.07	.73	.56	14.0	1.23	2.95	3.51		1.29	6.46	.43
FAGU022	6829	73.4	75.5	2.1	100	4AD	3.94	.43	4.90	3.60	94.0	2.54	1.95	13.30		8.50	15.25	.42
FAGU022	6830	75.5	77.4	1.9	53	4D4	3.87	.15	5.87	8.16	93.0	3.29	4.49	13.55		14.03	18.04	.58
FAGU022	6831	77.4	78.8	1.4	100	4D4	3.81	.16	5.30	5.60	90.0	2.19	2.38	19.10		10.90	21.48	.51
FAGU022	6832	78.8	80.8	2.0	100	4D0	3.82	.23	5.10	4.70	95.0	2.40	2.58	20.40		9.80	22.98	.48
FAGU022	6833	80.8	82.8	2.0	100	4D0	3.71	.18	3.30	2.20	59.0	2.40	2.17	22.30		5.50	24.47	.40
FAGU022	6834	82.8	84.6	1.8	100	4D4	3.76	.28	6.40	5.10	112.0	3.43	2.09	18.50		11.50	20.59	.44
FAGU022	6835	84.6	85.6	1.0	100	4D0	3.77	.13	3.60	4.20	62.0	1.92	2.45	21.30		7.80	23.75	.54
FAGU153	6836	.0	3.0	3.0	50	4A4	3.49	.04	5.10	10.10	82.0	1.10	1.46	11.40		15.20	12.86	.66
FAGU153	6837	3.0	5.3	2.3	91	4A4	3.38	.11	3.20	6.10	69.0	1.17	1.26	14.10		9.30	15.36	.66
FAGU153	6838	5.3	7.3	2.0	100	4A4	3.35	.07	4.40	8.00	71.0	1.10	1.34	11.00		12.40	12.34	.65
FAGU153	6839	7.3	9.1	1.8	100	4A4	3.36	.06	4.80	12.70	82.0	1.23	1.44	7.20		17.50	8.64	.73
FAGU153	6840	9.1	11.3	2.2	95	4A4	3.35	.03	5.00	11.50	84.0	1.17	1.38	10.00		16.50	11.38	.70
FAGU153	6841	11.3	13.1	1.8	100	4A4	3.62	.07	4.70	8.80	79.0	1.44	1.27	15.50		13.50	16.77	.65
FAGU153	6842	13.1	15.2	2.1	100	4A4	3.38	.05	3.20	8.10	60.0	1.10	1.17	13.20		11.30	14.37	.72
FAGU153	6843	15.2	16.8	1.6	100	4A4	3.26	.05	1.69	4.20	35.0	.75	1.36	13.20		5.89	14.56	.71
FAGU153	6844	16.8	18.3	1.5	100	4A31	3.67	.06	1.63	3.80	38.0	.89	1.47	21.90		5.43	23.37	.70
FAGU153	6845	18.3	19.8	1.5	100	4A41	3.47	.03	1.62	4.30	35.0	1.58	1.20	16.30		5.92	17.50	.73
FAGU153	6846	19.8	21.7	1.9	79	4A41	3.24	.11	1.90	4.10	36.0	1.92	1.14	12.80		6.00	13.94	.68
FAGU153	6847	21.7	23.2	1.5	100	4A41	3.33	.08	2.90	6.90	56.0	1.92	1.51	13.10		9.80	14.61	.70
FAGU153	6848	23.2	25.2	2.0	80	4E0	4.53	.31	.66	1.07	25.0	2.40	1.42	40.60		1.73	42.02	.62
FAGU153	6849	25.2	26.9	1.7	94	4E0	4.66	.27	.83	1.56	25.0	1.92	1.50	40.70		2.39	42.20	.65
FAGU153	6850	26.9	29.6	2.7	100	4A41	3.45	.13	3.80	7.60	69.0	2.06	1.54	14.20		11.40	15.74	.67
FAGU153	6851	29.6	30.5	.9	78	4E0	4.70	.25	1.82	1.78	36.0	1.03	1.61	40.90		3.60	42.51	.49
FAGU153	6852	30.5	32.0	1.5	93	4E4	4.43	.28	6.00	9.30	103.0	1.17	2.01	35.40		15.30	37.41	.61
FAGU153	6853	32.0	33.5	1.5	93	4AE4	3.67	.20	5.70	7.40	122.0	1.03	1.83	16.70		13.10	18.53	.56
FAGU153	6854	33.5	35.1	1.6	63	4E41	4.45	.07	11.50	19.60	185.0	2.88	2.08	16.30		31.10	18.38	.63
FAGU153	6855	35.1	35.6	.5	80	4G4	4.78	.25	8.00	15.30	162.0	4.05	2.60	20.10		23.30	22.70	.66
FAGU153	6856	35.6	36.6	1.0	80	4E4	4.37	.13	6.30	13.00	113.0	1.10	3.59	15.00		19.30	18.59	.67
FAGU153	6857	36.6	37.0	.4	100	4A1	3.52	.08	2.30	2.60	52.0	1.99	1.60	15.70		4.90	17.30	.53
FAGU153	6858	37.0	38.1	1.1	91	4G4	4.75	.25	6.10	7.70	115.0	2.13	.72	30.20		13.80	30.92	.56
FAGU153	6859	38.1	40.0	1.9	74	5C4	3.38	.05	.70	.61	16.0	4.66	4.41	11.70		1.31	16.11	.47
FAGU153	6860	40.0	41.6	1.6	75	4G4	4.94	.29	7.00	9.40	136.0	2.47	.96	22.80		16.40	23.76	.57
FAGU153	6861	41.9	42.7	.8	100	4A1	3.46	.05	.89	1.58	19.0	1.10	1.21	15.10		2.47	16.31	.64
FAGU151	6862	.0	2.2	2.2	73	4E4	4.07	.15	6.30	10.80	102.0	2.61	1.70	18.70		17.10	20.40	.63
FAGU151	6863	2.2	2.8	.6	100	4E*4	4.29	.35	6.10	8.50	89.0	2.19	2.18	27.90		14.60	30.08	.58
FAGU151	6864	2.8	4.1	1.3	92	4E4	4.96	.30	10.50	16.00	137.0	4.11	1.42	25.20		26.50	26.62	.60

DDH	SAMPLE	---DEPTHS---		INT M	REC %	ROCK UNIT	S.G.	CU %	PB %	ZN %	AG G/MT	AU G/MT	PO %	PY %	BAG %	PB+ZN %	PC+PY %	ZN RATIO
		FROM	TO															
FAGU151	6865	4.1	4.6	.5	80	4G0	5.01	.09	7.20	.80	113.0	1.10	.97	17.40		8.00	18.37	.10
FAGU151	6866	4.6	6.1	1.5	87	4E4	4.81	.04	4.70	5.80	62.0	1.17	2.41	19.10		10.50	21.51	.55
FAGU151	6867	6.1	7.4	1.3	100	4B5	3.41	.07	.12	.15	6.0	.69	2.49	14.30		.27	16.79	.56
FAGU151	6868	7.4	9.1	1.7	100	4A1	3.18	.01	.09	.08	7.0	.55	1.13	8.80		.17	9.93	.48
FAGU151	6869	9.1	11.1	2.0	100	4A41	3.18	.03	2.10	3.60	34.0	.55	1.43	10.00		5.70	11.43	.63
FAGU151	6870	11.1	13.1	2.0	100	4A41	3.24	.03	2.50	4.40	44.0	.75	.74	10.20		6.90	10.94	.64
FAGU151	6871	13.1	14.3	1.2	100	4A41	3.42	.13	2.90	6.50	56.0	1.65	1.49	13.30		9.40	14.79	.69
FAGU151	6872	14.3	15.4	1.1	100	4A41	3.40	.15	4.20	8.30	75.0	1.37	1.33	11.30		12.50	12.63	.66
FAGU151	6873	15.4	16.7	1.3	77	4D4	3.90	.22	9.70	10.90	151.0	1.51	1.68	15.40		20.60	17.08	.53
FAGU151	6874	16.7	18.3	1.6	100	4E4	4.13	.20	5.50	6.00	92.0	2.06	1.42	23.50		11.50	24.92	.52
FAGU151	6875	18.3	20.7	2.4	79	4E4	4.25	.33	3.50	3.60	57.0	1.85	2.18	30.60		7.10	32.78	.51
FAGU151	6876	54.6	55.4	.8	100	4G41	4.80	.13	9.00	8.40	134.0	2.47	3.14	15.30		17.40	18.44	.48
FAGU151	6877	55.4	57.8	2.4	87	4E0	4.69	.22	2.20	1.27	39.0	2.47	2.27	35.10		3.47	37.37	.37
FAGU151	6878	57.8	58.3	.5	80	4G41	4.86	.05	10.70	11.10	182.0	2.74	1.50	13.10		21.80	14.60	.51
FAGU151	6879	58.3	60.1	1.8	94	4E4	4.81	.17	3.90	3.40	57.0	.82	1.75	30.60		7.30	32.35	.47
FAGU151	6880	60.1	62.4	2.3	91	4E48	4.73	.15	13.40	12.30	177.0	2.40	8.58	15.20		25.70	23.78	.48
FAGU151	6881	62.4	65.1	2.7	70	4E4	4.58	.65	7.60	6.20	137.0	2.26	3.56	24.10		13.80	27.66	.45
FAGA005	6882	127.9	129.1	1.2	100	4E4#	4.35	.19	11.10	10.10	145.0	.34	2.83	23.00		21.20	25.83	.48
FAGA005	6883	129.1	129.6	.5	100	4E4	4.50	.33	6.60	4.80	87.0	.34	2.63	30.70		11.40	33.33	.42
FAGA005	6884	129.6	130.0	.4	100	4L47	4.46	.10	4.80	4.30	58.0	.21	6.95	12.10		9.10	19.05	.47
FAGA005	6885	155.2	155.9	.7	100	4A0		.03	.88	1.55	14.0					2.43		.64
FAGA005	6886	159.0	159.5	.5	100	4A1		.05	.89	1.32	14.0					2.21		.60
FAGA005	6887	159.5	160.5	1.0	100	4L0		.04	.43	.61	10.0					1.04		.59
FAGA099	6888	138.5	139.1	.6	100	4EL4	4.05	.10	4.70	4.40	89.0	.96	5.62	20.30		9.10	25.92	.48
FAGA099	6889	139.1	139.5	.4	75	4H4	4.33	.12	4.10	4.80	67.0	.48	12.52	23.90		8.90	36.42	.54
FAGA099	6890	140.4	141.2	.8	100	4E4	4.72	.10	9.50	6.10	137.0	1.30	4.43	28.10		15.60	32.53	.39
FAGA099	6891	141.2	142.9	1.7	100	4G4	4.80	.13	3.40	5.90	62.0	.96	1.23	19.00		9.30	20.23	.63
FAGA099	6892	142.9	144.9	2.0	100	4G4	4.61	.18	3.00	4.30	53.0	1.30	2.62	27.60		7.30	30.22	.59
FAGA099	6893	144.9	147.5	2.6	100	4E4	4.25	.23	3.10	3.70	50.0	1.17	3.50	13.40		6.80	16.90	.54
FAGA099	6894	147.5	149.4	1.9	100	4G4	4.69	.08	5.70	7.10	94.0	.62	2.63	15.20		12.80	17.83	.55
FAGA099	6895	149.4	151.4	2.0	100	4G4	4.12	.02	3.70	6.80	65.0	.41	1.48	12.00		10.50	13.48	.65
FAGA099	6896	151.4	152.7	1.3	100	4G4	4.33	.03	4.30	7.30	79.0	.55	1.44	13.30		11.60	14.74	.63
FAGA099	6897	152.7	154.1	1.4	100	4G0	4.35	.04	.30	8.30	83.0	.48	1.75	11.20		8.60	12.95	.97
FAGA099	6898	154.1	155.3	1.2	100	4E84	4.38	.24	4.10	3.00	79.0	1.51	4.57	31.20		7.10	35.77	.42
FAGA099	6899	155.3	157.6	2.3	100	4C3	3.97	.28	1.04	.42	28.0	2.19	3.02	27.60		1.46	30.62	.29
FAGA099	6900	157.6	159.1	1.5	100	4C3	3.81	.24	.38	.20	18.0	1.10	2.01	27.20		.58	29.21	.34
FAGU083	6901	8.3	9.9	1.6	69	5C4*	2.99	.03	.36	.56	11.0	.27	2.52	6.50		.92	9.02	.61
FAGU083	6902	9.9	11.3	1.4	100	4A1	3.01	.05	1.25	1.94	24.0	.41	3.21	5.60		3.19	8.81	.61
FAGU083	6903	11.3	13.7	2.4	75	4L1	2.91	.06	.79	1.49	19.0	.41	2.14	4.32		2.28	6.46	.65
FAGU083	6904	13.7	15.5	1.8	22	4L1	3.04	.07	1.17	2.70	25.0	.27	1.15	8.20		3.87	9.35	.70
FAGU083	6905	15.5	16.6	1.1	100	4A4	3.26	.01	3.20	6.80	59.0	.55	1.39	10.40		10.00	11.79	.68
FAGU083	6906	16.6	17.8	1.2	92	4E0	3.08	.03	7.30	1.48	121.0	.89	1.22	22.40		8.78	23.62	.17
FAGU083	6907	17.8	20.5	2.7	67	4A4	3.35	.01	4.10	9.70	89.0	.89	1.25	9.80		13.80	11.05	.70
FAGU083	6908	20.5	23.5	3.0	57	4E4	3.70	.05	4.00	13.30	123.0	.82	2.97	11.80		17.30	14.77	.77
FAGU085	6909	8.9	10.7	1.8	100	4A0	3.36	.16	.70	1.23	20.0	1.17	3.03	15.70		1.93	18.73	.64
FAGU085	6910	10.7	12.2	1.5	100	4A0	3.17	.09	.80	2.00	19.0	.48	3.39	6.20		2.80	9.59	.71
FAGU085	6911	12.2	13.9	1.7	76	4A0	2.97	.08	.64	1.37	16.0	.21	2.96	5.67		2.01	8.63	.68
FAGU085	6912	13.9	14.4	.5	60	4A14	3.17	.05	2.60	6.70	44.0	.55	3.31	6.40		9.30	9.71	.72
FAGU085	6913	14.4	15.2	.8	100	4E4	4.61	.01	.40	9.00	79.0	.82	1.42	33.00		9.40	34.42	.96
FAGU085	6914	15.2	17.0	1.8	100	4E4	4.67	.15	6.90	7.80	127.0	.82	1.35	26.90		14.70	28.25	.53

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAO	PB+ZN	PC+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGUC85	6915	17.0	19.1	2.1	71	4E4	4.70	.13	7.70	20.80	142.0	.96	1.19	25.00		28.50	26.19	.73
FAGU085	6916	19.1	21.0	1.9	95	4E4	4.67	.13	6.40	15.20	119.0	.96	.95	29.40		21.60	30.35	.70
FAGU085	6917	21.0	22.5	1.5	100	4E4	4.10	.02	5.80	13.00	109.0	.89	1.44	21.70		18.80	23.14	.69
FAGU085	6918	22.5	23.3	.8	100	4E51	2.90	.03	3.70	8.40	64.0	1.10	1.44	20.20		12.10	21.64	.69
FAGU015	6919	19.9	24.4	4.5	29	4E4	4.54	.27	4.50	2.80	65.0	1.65	4.02	31.50		7.30	35.52	.38
FAGU015	6920	24.4	26.7	2.3	83	4E4	4.67	.23	3.00	2.70	64.0	1.44	3.08	35.30		5.70	38.38	.47
FAGU015	6921	26.7	27.6	.9	78	4GE#	4.89	.14	6.50	6.20	86.0	1.51	4.57	21.60		12.70	26.17	.49
FAGU015	6922	27.6	28.1	.5	80	4E48	4.86	.22	7.60	6.30	105.0	1.10	7.70	23.70		13.90	31.40	.45
FAGU015	6923	28.1	29.1	1.0	90	4GE	4.67	.12	11.40	7.00	158.0	1.51	2.12	24.00		18.40	26.12	.38
FAGU015	6924	29.1	30.5	1.4	71	4L74	3.69	.25	3.00	2.80	39.0	.48	9.68	15.00		5.80	24.68	.48
FAGU015	6925	67.1	67.9	.8	100	4D4	4.11	.13	5.30	8.10	97.0	.96	1.53	22.50		13.40	24.03	.60
FAGU015	6926	67.9	68.6	.7	100	4L52	3.21	.07	.55	1.38	9.0	.34	5.47	8.60		1.93	14.07	.72
FAGU015	6927	68.6	70.4	1.8	44	4G4	4.76	.19	7.10	10.90	130.0	.75	1.66	24.90		18.00	26.56	.61
FAGU015	6928	70.4	71.2	.8	75	4D4	3.66	.13	6.60	9.10	134.0	1.03	1.83	31.30		15.70	33.13	.58
FAGU015	6929	108.2	112.8	4.6	37	4D43	3.98	.33	6.50	7.90	119.0	1.92	2.66	19.20		14.40	21.86	.55
FAGU015	6930	112.8	114.0	1.2	100	4E1	4.43	.33	1.65	2.60	43.0	1.58	1.74	34.30		4.25	36.04	.61
FAGU015	6931	114.0	114.9	.9	67	4D4	3.82	.30	4.30	7.80	74.0	1.92	2.25	16.60		12.10	18.85	.64
FAGU015	6932	114.9	116.9	2.0	90	4E1	5.01	.40	2.20	2.80	43.0	2.26	1.51	34.90		5.00	36.41	.56
FAGU015	6933	116.9	118.3	1.4	93	4C0	4.54	.37	2.30	2.80	46.0	1.85	3.78	30.90		5.10	34.68	.55
FAGU015	6934	118.3	120.0	1.7	82	4D0	4.21	.42	3.00	6.40	56.0	1.78	3.01	25.90		9.40	28.91	.68
FAGU015	6935	120.0	121.2	1.2	100	4D53	3.80	.40	3.40	4.90	66.0	2.54	2.16	16.90		8.30	19.06	.59
FAGU015	6936	121.2	123.6	2.4	67	4C0	3.93	.27	1.60	1.57	30.0	1.44	1.93	25.40		3.17	27.33	.50
FAGU015	6937	123.6	125.9	2.3	78	4D0	3.99	.50	3.00	6.10	56.0	.75	1.69	22.70		9.10	24.39	.67
FAGU015	6938	125.9	127.7	1.8	89	4C0	3.53	.26	1.39	3.40	32.0	1.17	1.65	19.20		4.79	20.85	.71
FAGU015	6939	171.7	172.2	.5	80	4K0	4.47	.15	.50	.53	23.0	1.10	4.12	34.80		1.03	38.92	.51
FAGU015	6940	172.2	173.9	1.7	82	4D*8	3.65	.07	2.80	2.90	39.0	.89	2.91	16.60		5.70	19.51	.51
FAGU015	6941	173.9	175.7	1.8	89	4D*8	3.94	.05	4.80	4.10	55.0	.89	4.06	19.10		8.90	23.16	.46
FAGU015	6942	175.7	177.9	2.2	91	4E86	4.38	.30	2.50	2.90	44.0	1.10	6.82	27.80		5.40	34.62	.54
FAGU015	6943	177.9	179.8	1.9	100	4DC	3.89	.34	2.90	3.20	41.0	.89	7.38	18.30		6.10	25.68	.52
FAGU015	6944	179.8	181.4	1.6	100	4D0	3.94	.22	3.00	2.80	41.0	.89	6.19	21.10		5.80	27.29	.48
FAGU015	6945	181.4	182.9	1.5	100	4LE	3.45	.13	3.00	2.10	38.0	.48	3.49	14.40		5.10	17.89	.41
FAGU015	6946	182.9	184.0	1.1	91	4LE	3.85	.14	2.50	2.10	42.0	.69	4.86	22.20		4.60	27.06	.46
FAGU015	6947	184.0	184.8	.8	100	4A0	2.99	.08	.54	1.03	20.0	1.03	1.08	6.60		1.57	7.68	.66
FAGU015	6948	184.8	185.9	1.1	100	4GEL	3.71	.26	8.70	17.90	177.0	1.30	4.89	21.80		26.60	26.69	.67
FAGA024	6949	178.6	178.9	.3	100	4E4	4.53	.26	8.70	17.90	177.0	2.26	3.37	18.10		26.60	21.47	.67
FAGU058	6950	.0	2.1	2.1	71	4E4	4.74	.26	2.70	3.10	41.0	1.85	1.26	37.29		5.80	38.55	.53
FAGU058	6951	2.1	4.2	2.1	100	4E4	4.93	.28	4.80	7.40	59.0	2.81	1.84	35.20		12.20	37.04	.61
FAGU058	6952	4.2	5.9	1.7	76	4G4	4.81	.27	6.40	9.30	105.0	1.99	.85	21.40		15.70	22.25	.59
FAGU058	6953	5.9	7.6	1.7	88	4G4	4.68	.17	7.20	12.70	163.0	2.06	.71	15.20		19.90	15.91	.64
FAGU058	6954	7.6	9.0	1.4	93	4E4	4.59	.07	7.50	12.40	99.0	1.17	1.61	27.60		19.90	29.21	.62
FAGU058	6955	9.0	9.7	.7	71	5C*	2.94	.01	.18	.31	2.0	.21	6.70	1.90		.49	8.60	.63
FAGU058	6956	9.7	10.2	.5	100	4L0	3.37	.03	.66	1.05	7.0	.27	3.97	13.20		1.71	17.17	.61
FAGU058	6957	10.2	11.7	1.5	87	4E4	3.75	.07	1.77	3.30	36.0	.62	6.47	21.40		5.07	27.87	.65
FAGU058	6958	11.7	13.0	1.3	92	5A6	3.01	.06	.43	.59	3.0	.21	3.52	4.10		1.02	7.62	.58
FAGU058	6959	13.0	13.7	.7	86	5C3	3.69	.16	3.90	7.10	80.0	.41	6.39	15.40		11.00	21.79	.65
FAGU058	6960	13.7	14.7	1.0	100	5B12	2.99	.04	.62	1.31	6.0	1.17	3.39	2.48		1.93	5.87	.68
FAGU058	6961	14.7	15.7	1.0	80	4E4	4.84	.28	9.60	19.80	139.0	.34	2.55	20.60		29.40	23.15	.67
FAGU058	6962	15.7	16.6	.9	89	4G4	4.56	.25	5.80	15.90	86.0	.48	.95	16.70		21.70	17.65	.73
FAGU058	6963	16.6	17.6	1.0	100	4E4	4.60	.41	5.80	15.50	87.0	1.85	1.04	23.90		21.30	24.94	.73
FAGU058	6964	17.6	18.5	.9	100	4E4	4.40	.17	7.40	18.00	120.0	1.99	1.41	24.20		25.40	25.61	.71

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAO	PB+ZN	PC+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGU058	6965	26.6	28.3	1.7	88	4E10	3.21	.11	.76	.80	8.0	.21	8.09	12.40		1.56	20.49	.51
FAGU058	6966	87.1	88.3	1.2	92	4E84	4.43	.20	6.80	3.50	72.0	1.17	12.34	25.60		10.30	37.94	.34
FAGU058	6967	88.3	89.4	1.1	91	4E84	4.50	.21	8.00	3.40	97.0	1.78	6.39	28.80		11.40	35.19	.30
FAGU058	6968	89.4	91.1	1.7	82	4E0	4.46	.34	.55	.40	21.0	1.30	3.11	39.40		.95	42.51	.42
FAGU058	6969	91.1	92.7	1.6	94	4E0	4.44	.31	.52	.64	19.0	1.23	2.12	38.70		1.16	40.82	.55
FAGU058	6970	92.7	94.3	1.6	75	4E4	4.32	.15	4.70	4.30	78.0	1.58	2.80	30.10		9.00	32.90	.48
FAGU058	6971	94.3	96.3	2.0	95	4E0	4.57	.20	1.88	1.11	47.0	1.65	1.85	36.00		2.99	37.85	.37
FAGU058	6972	96.3	98.0	1.7	100	4E4	4.08	.20	3.20	1.60	59.0	1.51	4.77	28.60		4.80	33.37	.33
FAGU058	6973	98.0	98.6	.6	50	5D4\$	3.34	.15	.29	.18	14.0	.41	4.03	15.40		.47	19.43	.38
FAGU058	6974	98.6	99.8	1.2	75	4E4#	4.04	.08	5.93	7.20	92.0	.82	4.59	19.50		13.13	24.09	.55
FAGA001	6975	260.1	262.1	2.0	100	4KE		.23	.98	.96	23.0					1.94		.49
FAGA001	6976	262.1	262.5	.4	100	4C73	3.75	.13	1.77	2.52	26.0	.21	6.74	20.50		4.29	27.24	.59
FAGA014	6977	193.2	194.0	.8	100	4LH	3.96	.21	1.64	1.53	38.0	.34	5.58	25.20		3.17	30.78	.48
FAGAC14	6978	258.3	259.3	1.0	100	4A13		.16	.46	.35	16.0					.81		.43
FAGAC30	6979	144.5	145.4	.9	78	4E41	4.06	.10	8.80	17.90	150.0	1.17	3.07	16.30		26.70	19.37	.67
FAGA030	6980	145.4	146.4	1.0	90	5B21	2.98	.03	.41	.79	11.0	.21	1.29	3.27		1.20	4.56	.66
FAGA030	6981	146.4	148.2	1.8	100	4A4	3.13	.03	2.24	5.28	41.0	.69	1.06	9.10		7.52	10.16	.70
FAGA030	6982	148.2	148.7	.5	60	4A0	3.15	.08	1.51	1.14	38.0	.89	.98	12.80		2.65	13.78	.43
FAGA030	6983	148.7	149.7	1.0	100	4A1	2.91	.04	.52	1.25	14.0	.48	.77	5.37		1.77	6.14	.71
FAGA030	6984	149.7	151.2	1.5	33	FAULT	2.88	.06	.66	1.28	14.0	4.11	.63	4.68		1.94	5.31	.66
FAGA030	6985	151.2	153.7	2.5	84	4A1	2.97	.08	1.53	1.42	24.0	.82	.84	6.40		2.95	7.24	.48
FAGA030	6986	153.7	155.6	1.9	100	4A1	2.91	.06	1.97	2.13	26.0	1.17	.89	3.88		4.10	4.77	.52
FAGA030	6987	155.6	157.6	2.0	100	4L1	3.09	.05	1.41	2.67	24.0	.48	.92	3.55		4.08	4.47	.65
FAGA030	6988	157.6	158.9	1.3	100	5C4a	2.89	.01	.06	.16	3.0	.27	4.28	.72		.22	5.00	.73
FAGAC30	6989	158.9	161.3	2.4	13	4A14	3.08	.05	2.45	5.36	44.0	.75	1.93	6.60		7.81	8.53	.69
FAGA030	6990	161.3	163.0	1.7	100	5D4a	3.05	.02	.26	1.38	5.0	.27	5.80	2.09		1.64	7.89	.84
FAGA030	6991	163.0	164.6	1.6	94	5D4a	2.99	.02	.96	2.64	19.0	.34	3.81	2.23		3.60	6.04	.73
FAGAC30	6992	164.6	165.1	.5	100	5B46	3.02	.01	.13	.31	2.0	.27	3.84	1.21		.44	5.05	.70
FAGA030	6993	165.1	165.8	.7	86	10Q0	2.81	.02	.06	.09	1.0	.21	1.83	.81		.15	2.64	.60
FAGA030	6994	165.8	166.4	.6	100	5B46	2.97	.02	.06	.18	1.0	1.23	3.07	1.97		.24	5.04	.75
FAGA030	6995	166.4	169.0	2.6	92	4B4	3.03	.01	3.02	6.99	50.0	.41	3.38	1.88		10.01	5.26	.70
FAGA030	6996	169.0	171.0	2.0	100	4B4	3.02	.03	5.14	8.18	92.0	.89	1.67	1.25		13.32	2.92	.61
FAGA030	6997	177.4	179.3	1.9	100	4B4	2.88	.02	2.79	4.90	50.0	.48	1.07	.82		7.69	1.89	.64
FAGA030	6998	179.3	181.6	2.3	91	4B4	2.91	.02	3.40	6.58	60.0	.55	1.12	.64		9.98	1.76	.66
FAGA030	6999	181.6	183.3	1.7	100	4B4	2.94	.04	3.15	5.62	59.0	.69	1.18	1.57		8.77	2.75	.64
FAGAC30	7000	183.3	184.9	1.6	100	4B4	2.91	.03	2.34	4.33	44.0	.41	1.05	.98		6.67	2.03	.65
FAGA099	7001	159.1	161.2	2.1	100	4C3	3.78	.31	.32	.16	10.0	1.65	1.55	26.00		.48	27.55	.33
FAGAG99	7002	161.2	162.0	.8	88	5D4*		.04	.06	.06	3.0					.12		.50
FAGA099	7003	162.0	163.8	1.8	100	4C3		.24	.10	.09	3.0					.19		.47
FAGA099	7004	163.8	165.4	1.6	100	4C3		.33	.22	.39	7.0					.61		.64
FAGA099	7005	165.4	166.4	1.0	100	4C3		.33	.27	.34	9.0					.61		.56
FAGA099	7006	166.4	167.9	1.5	100	4C3		.36	.59	.34	15.0					.93		.37
FAGA099	7007	167.9	169.3	1.4	100	4C3	3.61	.20	3.00	1.69	47.0	.41	7.10	15.10		4.69	22.20	.36
FAGAG99	7008	169.3	170.6	1.3	100	4C7	3.57	.28	.61	.90	9.0	.41	12.00	13.70		1.51	25.70	.60
FAGA099	7009	170.6	172.3	1.7	100	4L4		.17	.25	.79	3.0					1.04		.76
FAGA099	7010	172.3	174.0	1.7	100	4L4		.05	.59	.94	10.0					1.53		.61
FAGA099	7011	174.0	175.8	1.8	94	4L4		.10	.71	1.15	11.0					1.86		.62
FAGA099	7012	175.8	177.6	1.8	100	4L4		.29	.34	.84	11.0					1.18		.71
FAGA099	7013	177.6	179.3	1.7	100	4L4		.08	.32	.50	8.0					.82		.61
FAGA099	7014	179.3	181.3	2.0	90	4L4		.03	.11	.26	5.0					.37		.70

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAG	PB+ZN	PO+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGA004	7015	163.7	164.7	1.0	70	4LHG	3.75	.10	2.90	3.40	62.0	.41	11.27	13.30		6.30	24.57	.54
FAGA004	7016	164.7	165.9	1.2	92	4E0	4.36	.21	3.60	2.50	82.0	1.23	4.41	31.90		6.10	36.31	.41
FAGA004	7017	165.9	168.6	2.7	89	4E0	2.97	.24	.23	.15	20.0	1.10	2.14	39.30		.38	41.44	.39
FAGA004	7018	168.6	169.0	.4	100	4E8	4.53	.29	.75	.47	38.0	1.71	4.05	37.80		1.22	41.85	.38
FAGA004	7019	169.0	169.6	.6	100	5D4a	2.59	.02	.17	.15	8.0	.27	4.18	1.61		.32	5.79	.47
FAGA004	7020	169.6	171.3	1.7	100	4E8G	4.38	.19	3.14	3.12	53.0	.96	5.50	9.10		6.26	14.60	.50
FAGA004	7021	244.6	245.7	1.1	100	4EA		.22	1.27	1.64	30.0					2.91		.56
FAGA004	7022	256.5	258.6	2.1	100	4A1		.14	.15	.40	10.0					.55		.73
FAGA004	7023	258.6	260.8	2.2	100	4A1		.18	.37	.74	15.0					1.11		.67
FAGA004	7024	260.8	261.6	.8	88	4E#4		.10	4.60	6.60	82.0					11.20		.59
FAGA004	7025	261.6	262.0	.4	100	4A0		.10	.65	.96	18.0					1.61		.60
FAGA004	7026	283.7	284.8	1.1	100	4E0		.06	.41	.50	16.0					.91		.55
FAGA004	7027	284.8	285.3	.5	60	5A0		.01	.12	.91	7.0					1.03		.88
FAGA004	7028	285.3	285.9	.6	83	4E0		.06	.08	.26	9.0					.34		.76
FAGA122	7029	120.6	122.2	1.6	94	4G4	4.16	.09	4.30	8.90	74.0	.89	1.51	25.60		13.20	27.11	.67
FAGA122	7030	122.2	123.0	.8	100	4DE	4.60	.22	5.90	7.60	133.0	.55	.98	28.42		13.50	29.40	.56
FAGA122	7031	135.4	137.8	2.4	100	4A3		.10	.18	.36	12.0					.54		.67
FAGA122	7032	137.8	140.3	2.5	100	4A3		.11	.70	1.12	16.0					1.82		.62
FAGA122	7033	140.3	141.0	.7	100	4E08		.29	.75	.70	27.0					1.45		.48
FAGA122	7034	141.0	143.5	2.5	64	4A3		.12	.09	.16	9.0					.25		.64
FAGA122	7035	143.5	146.0	2.5	56	4A3		.05	.15	.23	7.0					.38		.61
FAGA122	7036	146.0	148.5	2.5	64	4A3		.08	.20	.19	10.0					.39		.49
FAGA122	7037	148.5	150.0	1.5	100	4LC		.13	.19	.60	8.0					.79		.76
FAGA122	7038	160.6	163.5	2.9	100	4A31		.05	.03	.03	4.0					.06		.50
FAGA122	7039	163.5	166.4	2.9	52	4A31		.02	.04	.13	4.0					.17		.76
FAGA122	7040	166.4	169.2	2.8	50	4A31		.01	.03	.02	4.0					.05		.40
FAGA122	7041	169.2	172.0	2.8	86	4A31		.03	.01	.01	4.0					.02		.50
FAGA122	7042	199.0	202.1	3.1	74	4A31		.06	.13	.12	6.0					.25		.48
FAGA122	7043	202.1	203.0	.9	100	4G48	4.45	.11	4.60	5.50	73.0	.41	13.10	14.10		10.10	27.20	.54
FAGA122	7044	203.0	203.5	.5	100	4A31	2.88	.09	.10	.07	5.0	.21	3.19	27.20		.17	30.39	.41
FAGA122	7045	203.5	206.0	2.5	96	4EG8	4.02	.25	3.15	2.78	43.0	.96	7.81	26.60		5.93	34.41	.47
FAGA122	7046	206.0	208.6	2.6	100	4CG8	4.33	.27	2.70	1.91	41.0	1.17	8.06	17.20		4.61	25.26	.41
FAGA122	7047	208.6	211.2	2.6	100	4CG8	3.69	.27	2.62	2.02	37.0	1.65	7.64	18.40		4.64	26.04	.44
FAGA122	7048	211.2	213.7	2.5	100	5B23	2.86	.03	.07	.03	3.0	.14	1.87	1.14		.10	3.01	.30
FAGA122	7049	213.7	214.1	.4	100	4L23	3.02	.10	.55	.23	12.0	.62	3.04	3.34		.78	6.38	.29
FAGA122	7050	214.1	216.4	2.3	100	4EG8	3.93	.14	2.02	1.94	38.0	1.10	7.04	23.20		3.96	30.24	.49
FAGA122	7051	216.4	218.6	2.2	100	4EG8	4.45	.21	3.97	3.10	55.0	1.23	8.03	26.90		7.07	34.93	.44
FAGA122	7052	218.6	220.8	2.2	100	4EG8	4.21	.17	1.68	1.35	33.0	1.65	8.51	22.90		3.03	31.41	.45
FAGA122	7053	220.8	221.6	.8	62	5A1	2.91	.09	.30	.21	9.0	.55	2.29	3.50		.51	5.79	.41
FAGA122	7054	221.6	222.1	.5	60	4EG4	4.40	.07	3.50	5.10	56.0	1.03	4.81	29.70		8.60	34.51	.59
FAGA122	7055	222.1	222.6	.5	80	4B0	2.93	.15	1.85	6.90	43.0	1.23	1.49	3.02		8.75	4.51	.79
FAGU089	7056	.0	1.1	1.1	100	4L12	3.08	.07	.73	2.06	16.0	.48	1.33	6.50		2.79	7.83	.74
FAGU089	7057	1.1	3.0	1.9	79	4C0	3.05	.11	.62	1.28	14.0	.96	1.44	7.50		1.90	8.94	.67
FAGU089	7058	3.0	4.8	1.8	100	4L12	3.11	.02	2.08	4.20	38.0	.48	.99	1.87		6.28	2.86	.67
FAGU089	7059	4.8	6.7	1.9	100	4L12	2.94	.03	1.64	3.70	32.0	.48	1.49	1.14		5.34	2.63	.69
FAGU089	7060	6.7	9.1	2.4	100	4L12	3.03	.05	.75	1.14	14.0	.55	1.04	4.52		1.89	5.56	.60
FAGU089	7061	9.1	11.0	1.9	100	4L12	4.02	.08	1.00	1.10	20.0	.48	1.14	6.60		2.10	7.74	.52
FAGU089	7062	11.0	12.2	1.2	100	4A10	2.91	.05	1.57	2.30	31.0	.82	.87	4.45		3.87	5.32	.59
FAGU089	7063	12.2	14.8	2.6	100	4L12	2.90	.03	.41	2.01	32.0	.55	1.31	2.08		2.42	3.39	.83
FAGU089	7064	14.8	15.2	.4	100	4D0	2.91	.02	1.74	4.60	26.0	.48	1.14	1.13		6.34	2.27	.73

DDH	SAMPLE	---DEPTHS---		INT M	REC %	ROCK UNIT	S.G.	CU %	PB %	ZN %	AG G/MT	AU G/MT	PO %	PY %	BAO %	PB+ZN %	PG+PY %	ZN RATIO
		FROM	TO															
FAGU089	7065	15.2	16.8	1.6	94	4L12	2.87	.02	2.03	4.80	39.0	.41	.99	1.52		6.83	2.51	.70
FAGU089	7066	16.8	18.3	1.5	100	4L12	2.87	.03	1.43	2.80	27.0	.41	1.12	2.48		4.23	3.60	.66
FAGU089	7067	18.3	19.8	1.5	80	4E4	4.45	.18	8.70	16.00	127.0	1.71	.96	26.40		24.70	27.36	.65
FAGU089	7068	19.8	21.8	2.0	65	4E4	4.73	.13	7.70	15.40	158.0	1.17	1.00	27.70		23.10	28.70	.67
FAGU089	7069	21.8	24.1	2.3	78	4E41	3.89	.02	7.60	17.20	145.0	1.37	1.87	17.70		24.80	19.57	.69
FAGU089	7070	24.1	26.4	2.3	96	4E4	4.38	.07	10.00	22.00	165.0	1.23	1.70	21.20		32.00	22.90	.69
FAGU089	7071	26.4	26.9	.5	100	4A14	3.34	.11	1.86	5.90	32.0	.48	5.80	15.20		7.76	21.00	.76
FAGU089	7072	26.9	28.4	1.5	100	4E41	4.38	.10	8.50	16.60	155.0	1.17	2.60	14.40		25.10	17.00	.66
FAGU089	7073	28.4	30.5	2.1	33	5A61	2.99	.02	.53	1.12	14.0	.14	1.84	3.71		1.65	5.55	.68
FAGU089	7074	30.5	31.7	1.2	50	4E41	4.10	.12	8.70	12.80	170.0	1.58	2.41	18.10		21.50	20.51	.60
FAGA009	7075	125.0	127.2	2.2	95	4E4	3.60	.04	4.80	7.50	85.0	1.10	1.87	17.40		12.30	19.27	.61
FAGA009	7076	141.5	144.0	2.5	76	4A4	3.11	.05	2.40	6.00	51.0	.82	1.31	8.20		8.40	9.51	.71
FAGA009	7077	144.0	146.0	2.0	100	4A4	3.30	.08	4.50	8.50	81.0	1.03	1.94	4.44		13.00	6.38	.65
FAGA009	7078	159.9	160.2	.3	67	4K0		.01	.42	.35	15.0					.77		.45
FAGA009	7079	160.2	161.3	1.1	100	5D4		.02	.31	.33	12.0					.64		.52
FAGAC09	7080	161.3	162.2	.9	100	4K0\$		.01	.11	.13	8.0					.24		.54
FAGU059	7081	.0	2.0	2.0	95	4A4	3.37	.05	4.50	11.10	74.0	1.37	1.44	10.90		15.60	12.34	.71
FAGU059	7082	2.0	4.0	2.0	100	4A4	3.37	.04	2.90	6.20	55.0	.82	1.51	15.10		9.10	16.61	.68
FAGU059	7083	4.0	6.0	2.0	100	4A4	3.23	.06	4.20	8.10	73.0	1.23	1.35	9.80		12.30	11.15	.66
FAGU059	7084	6.0	7.8	1.8	100	4A4	3.32	.06	3.70	8.20	68.0	1.37	1.32	12.70		11.90	14.02	.69
FAGU059	7085	7.8	9.7	1.9	100	4E14	3.46	.03	5.80	13.50	98.0	1.03	1.55	10.30		19.30	11.85	.70
FAGU059	7086	9.7	10.6	.9	100	4D4	4.02	.10	9.50	16.90	165.0	1.65	1.64	7.40		26.40	9.04	.64
FAGU059	7087	10.6	12.8	2.2	100	4E14	3.82	.35	10.40	18.40	175.0	2.33	2.12	7.98		28.80	10.10	.64
FAGU059	7088	12.8	14.9	2.1	100	4E14	4.11	.14	9.20	18.40	158.0	2.06	1.98	11.30		27.60	13.28	.67
FAGU059	7089	14.9	17.0	2.1	100	4E14	4.55	.10	11.80	18.00	191.0	2.06	2.05	13.80		29.80	15.85	.60
FAGU059	7090	17.0	18.8	1.8	100	4E4	4.81	.21	6.40	7.00	92.0	1.71	1.73	33.70		13.40	35.43	.52
FAGU059	7091	18.8	20.0	1.2	100	4E4	4.65	.07	11.00	18.60	167.0	1.92	2.53	22.30		29.60	24.83	.63
FAGU059	7092	20.0	21.1	1.1	100	4E4	4.55	.09	10.00	17.20	156.0	2.06	2.15	22.70		27.20	24.85	.63
FAGU059	7093	21.1	23.1	2.0	100	4G4	4.69	.10	6.30	10.00	110.0	1.37	.62	17.10		16.30	17.72	.61
FAGU059	7094	23.1	25.1	2.0	100	4G4	4.72	.22	6.90	10.50	123.0	1.92	.65	19.40		17.40	20.05	.60
FAGU059	7095	25.1	27.1	2.0	100	4G4	4.70	.22	6.80	11.00	112.0	2.13	2.82	21.60		17.80	24.42	.62
FAGU059	7096	27.1	29.1	2.0	100	4G4	4.61	.24	6.50	10.50	133.0	1.92	.91	19.80		17.00	20.71	.62
FAGU059	7097	29.1	31.1	2.0	100	4G4	4.64	.16	8.30	12.50	143.0	1.51	1.27	21.80		20.80	23.07	.60
FAGU059	7098	31.1	32.8	1.7	82	4G4	4.71	.27	6.60	10.00	124.0	1.10	.94	23.40		16.60	24.34	.60
FAGU059	7099	32.8	33.8	1.0	100	4E4	4.62	.18	9.60	15.90	150.0	1.17	2.51	14.00		25.50	16.51	.62
FAGU059	7100	33.8	35.2	1.4	100	4E4	4.89	.22	11.00	15.10	157.0	.82	1.98	22.30		26.10	24.28	.58
FAGA030	7101	184.9	187.5	2.6	100	4A14	2.99	.05	3.40	3.30	59.0	.75	.96	3.51		6.70	4.47	.49
FAGA030	7102	187.5	189.8	2.3	91	4A14	2.92	.03	2.90	4.20	49.0	.82	.98	1.69		7.10	2.67	.59
FAGA030	7103	189.8	190.8	1.0	20	4L04	2.89	.02	1.56	4.30	29.0	.75	1.18	1.84		5.86	3.02	.73
FAGA030	7104	190.8	192.2	1.4	100	4A1	2.85	.01	1.25	3.20	21.0	.55	1.01	.27		4.45	1.28	.72
FAGA030	7105	192.2	193.2	1.0	60	4L0	3.00	.02	.61	2.00	12.0	.34	1.75	.20		2.61	1.95	.77
FAGAC30	7106	193.2	195.3	2.1	76	4A1	2.82	.02	1.03	2.10	19.0	.34	.79	1.40		3.13	2.19	.67
FAGA030	7107	195.3	196.9	1.6	94	4A14	3.46	.05	2.13	4.40	45.0	.55	1.99	4.38		6.53	6.37	.67
FAGA030	7108	196.9	198.7	1.8	100	4A134	3.40	.04	3.00	4.70	54.0	.69	2.52	14.20		7.70	16.72	.61
FAGA030	7109	198.7	200.9	2.2	95	4A13	3.77	.07	2.40	.05	46.0	1.17	1.18	18.80		2.45	19.98	.02
FAGA030	7110	200.9	201.6	.7	71	4A314	4.01	.09	3.60	1.87	70.0	1.37	1.83	28.50		5.47	30.33	.34
FAGA030	7111	201.6	202.0	.4	75	4A31	3.89	.08	.91	1.62	22.0	.75	2.34	25.35		2.53	27.69	.64
FAGA030	7112	202.0	202.5	.5	100	4C0	3.36	.08	2.08	.76	31.0	1.71	1.37	15.60		2.84	16.97	.27
FAGA030	7113	213.8	216.3	2.5	92	4D45	3.50	.03	4.80	6.70	83.0	.96	1.85	13.70		11.50	15.55	.58
FAGA030	7114	216.3	217.1	.8	100	4D4	3.31	.03	4.70	10.90	83.0	1.78	1.82	8.30		15.60	10.12	.70

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAO	PB+ZN	PO+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGA030	7115	217.1	217.7	.6	67	4D45	3.55	.04	6.50	13.60	115.0	1.23	2.19	10.90		20.10	13.09	.68
FAGA030	7116	217.7	219.2	1.5	93	4A41	3.24	.04	3.20	6.80	65.0	1.30	1.49	9.90		10.00	11.39	.68
FAGA030	7117	219.2	219.8	.6	100	4L1	2.95	.02	.21	1.21	4.0	1.03	1.98	3.14		1.42	5.12	.85
FAGA030	7118	219.8	221.5	1.7	88	4A4	3.50	.06	6.50	10.00	110.0	1.44	1.55	11.50		16.50	13.05	.61
FAGA030	7119	221.5	222.6	1.1	91	4D4	3.79	.03	9.40	16.40	158.0	1.51	2.32	10.60		25.80	12.92	.64
FAGA030	7120	222.6	225.0	2.4	100	4A41	3.58	.08	7.40	11.90	111.0	1.30	1.81	10.10		19.30	11.91	.62
FAGA030	7121	225.0	225.7	.7	71	4A13	3.66	.11	1.75	2.40	30.0	1.44	2.07	19.39		4.15	21.46	.58
FAGA030	7122	225.7	227.4	1.7	88	4L0		.02	.43	.91	8.0					1.34		.68
FAGA030	7123	227.4	231.2	3.8	55	4L0		.01	.75	1.00	10.0					1.75		.57
FAGA030	7124	254.1	255.3	1.2	92	4E4	4.39	.12	3.10	6.70	58.0	1.30	2.71	27.30		9.80	30.01	.68
FAGAC30	7125	255.3	255.9	.6	83	4A4	3.34	.07	5.50	10.20	86.0	1.03	2.67	5.70		15.70	8.37	.65
FAGAC30	7126	255.9	257.1	1.2	100	4A1	3.43	.08	.88	1.36	17.0	.75	1.98	13.00		2.24	14.98	.61
FAGA030	7127	257.1	257.7	.6	83	4A4	3.28	.07	4.80	5.60	68.0	1.58	1.32	10.20		10.40	11.52	.54
FAGA030	7128	257.7	261.1	3.4	59	4A1	3.12	.08	.56	1.15	15.0	.62	1.35	11.50		1.71	12.85	.67
FAGA030	7129	261.1	263.1	2.0	75	4A1	3.35	.10	.34	.96	13.0	.41	1.21	16.00		1.30	17.21	.74
FAGA030	7130	263.1	265.3	2.2	64	4A1	3.36	.10	.72	1.32	15.0	1.17	1.22	12.50		2.04	13.72	.65
FAGA030	7131	279.4	281.8	2.4	100	4A1		.17	.73	1.31	20.0					2.04		.64
FAGA030	7132	281.8	282.7	.9	89	5B21		.08	.17	.44	7.0					.61		.72
FAGA030	7133	282.7	282.9	.2	100	4A4		.09	5.10	11.50	70.0					16.60		.69
FAGA030	7134	300.8	302.7	1.9	79	4L7		.26	1.46	1.10	21.0					2.56		.43
FAGA030	7135	340.5	340.9	.4	100	4G4\$	3.91	.11	5.40	7.50	85.0	1.10	2.78	12.40		12.90	15.18	.58
FAGA030	7136	340.9	342.0	1.1	82	4L0	2.88	.05	.14	.16	4.0	.21	3.95	2.00		.30	5.95	.53
FAGA030	7137	342.0	342.7	.7	86	4E4*	3.59	.13	3.50	3.80	56.0	1.03	4.45	15.70		7.30	20.15	.52
FAGU173	7138	.0	3.0	3.0	20	4DE	3.59	.35	1.38	3.60	32.0	1.03	4.29	19.30		4.98	23.59	.72
FAGU173	7139	13.8	15.8	2.0	75	4CL	3.07	.15	.21	.45	6.0	.41	4.19	9.00		.66	13.19	.68
FAGU173	7140	15.8	18.3	2.5	36	4A31	2.90	.06	.53	.81	8.0	.41	1.52	4.40		1.34	5.92	.60
FAGU173	7141	18.3	20.0	1.7	41	5A0		.05	.27	.45	7.0					.72		.63
FAGU173	7142	20.0	20.8	.8	63	5B0		.01	.01	.02	2.0					.03		.67
FAGU173	7143	20.8	22.8	2.0	90	4A0		.11	.32	.72	8.0					1.04		.69
FAGU173	7144	22.8	24.8	2.0	95	4A0		.19	.05	.38	2.0					.43		.88
FAGU173	7145	24.8	26.9	2.1	62	4A0		.21	.18	.27	6.0					.45		.60
FAGU173	7146	26.9	29.0	2.1	43	4A0		.07	.06	.06	3.0					.12		.50
FAGU173	7147	29.0	31.5	2.5	84	4L1?		.01	.02	.01	2.0					.03		.33
FAGU173	7148	31.5	34.5	3.0	83	4A0		.09	.97	.23	20.0					1.20		.19
FAGU173	7149	34.5	37.0	2.5	100	4E8		.07	.04	.02	50.0					.06		.33
FAGU173	7150	37.0	39.1	2.1	95	4GL	3.39	.11	1.58	1.75	27.0	.48	4.53	14.30		3.33	18.83	.53
FAGU173	7151	39.1	40.1	1.0	90	4L13		.03	.01	.03	3.0					.04		.75
FAGU173	7152	40.1	41.2	1.1	100	4A3		.20	.16	.20	12.0					.36		.56
FAGU173	7153	41.2	42.4	1.2	92	4E0		.10	.45	.39	16.0					.84		.46
FAGU173	7154	42.4	45.7	3.3	97	4EL8	4.37	.18	1.39	1.37	35.0	.41	7.04	16.83		2.76	23.87	.50
FAGU173	7155	45.7	47.4	1.7	100	4E81	4.53	.10	.50	.39	20.0	.55	8.20	27.20		.89	35.40	.44
FAGU173	7156	47.4	49.4	2.0	90	4LD	3.60	.18	1.04	1.23	23.0	2.81	5.20	9.80		2.27	15.00	.54
FAGU173	7157	49.4	51.8	2.4	46	4A3		.09	.19	.46	9.0					.65		.71
FAGU173	7158	51.8	54.1	2.3	78	4AE		.09	.14	.24	7.0					.38		.63
FAGU173	7159	54.1	56.4	2.3	70	4AE		.02	.03	.08	4.0					.11		.73
FAGU169	7160	.0	4.6	4.6	41	4CA3		.25	.02	.64	11.0					.66		.97
FAGU169	7161	4.6	6.6	2.0	90	4CA3		.15	.26	.43	12.0					.69		.62
FAGU169	7162	6.6	9.6	3.0	70	4A31		.21	.04	.40	10.0					.44		.91
FAGU169	7163	9.6	12.6	3.0	13	4A31		.12	.04	.66	10.0					.70		.94
FAGU169	7164	12.6	15.6	3.0	60	4A31		.19	.04	.20	10.0					.24		.83

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAO	PS+ZN	PC+PY	ZN	
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO	
FAGU169	7165	15.6	18.6	3.0	70	4A31		.17	.11	.32	14.0							.43	.74
FAGU169	7166	18.6	21.6	3.0	60	4A31		.13	.04	.17	7.0							.21	.81
FAGU169	7167	21.6	24.6	3.0	70	4A31		.15	.13	.18	10.0							.31	.58
FAGU169	7168	24.6	27.6	3.0	80	4A31		.07	.05	.16	6.0							.21	.76
FAGU169	7169	27.6	30.6	3.0	83	4A31		.08	.02	.13	5.0							.15	.87
FAGU169	7170	30.6	33.6	3.0	100	4A31		.06	.01	.16	5.0							.17	.94
FAGU169	7171	33.6	36.6	3.0	100	4A31		.13	.01	.23	7.0							.24	.96
FAGU169	7172	36.6	39.6	3.0	87	4A31		.11	.01	.16	6.0							.17	.94
FAGU169	7173	39.6	42.6	3.0	73	4A31		.11	.01	.13	6.0							.14	.93
FAGU169	7174	42.6	45.7	3.1	52	4A31		.12	.02	.24	5.0							.26	.92
FAGU177	7175	.0	3.1	3.1	90	4CL		.43	.13	.30	110.0							.43	.70
FAGU177	7176	3.1	6.3	3.2	91	4A31	3.38	.19	1.00	1.17	20.0	1.10	2.65	13.10			2.17	15.75	.54
FAGU177	7177	6.3	8.0	1.7	88	4CL		.18	.84	1.00	19.0							1.84	.54
FAGU177	7178	8.0	10.5	2.5	92	4A31		.20	.28	.75	12.0							1.03	.73
FAGU177	7179	10.5	13.0	2.5	92	4A31		.17	.16	.51	9.0							.67	.76
FAGU177	7180	13.0	15.5	2.5	76	4A31		.14	.06	.50	6.0							.56	.89
FAGU177	7181	15.5	18.0	2.5	100	4A31		.16	.61	.82	20.0							1.43	.57
FAGU177	7182	18.0	20.5	2.5	96	4A31		.21	.07	.26	9.0							.33	.79
FAGU177	7183	20.5	23.1	2.6	100	4A31		.31	.07	.15	12.0							.22	.68
FAGU177	7184	23.1	25.7	2.6	100	4A31		.29	.06	.30	12.0							.36	.83
FAGU177	7185	25.7	28.3	2.6	42	4A31		.13	.09	.27	6.0							.36	.75
FAGU177	7186	28.3	30.9	2.6	88	4A31		.10	.13	.38	9.0							.51	.75
FAGU177	7187	30.9	33.5	2.6	100	4A31		.12	.14	.25	8.0							.39	.64
FAGU177	7188	33.5	36.1	2.6	77	4A31		.07	.26	.34	7.0							.60	.57
FAGU177	7189	36.1	39.3	3.2	87	5D4*	2.97	.04	1.62	2.70	23.0	.48	4.08	3.01			4.32	7.09	.62
FAGU177	7190	39.3	41.2	1.9	63	4A3		.10	.14	.34	6.0							.48	.71
FAGU177	7191	41.2	43.2	2.0	75	4A3		.10	.03	.14	3.0							.17	.82
FAGU177	7192	43.2	45.2	2.0	100	4A3		.10	.09	.14	4.0							.23	.61
FAGU177	7193	45.2	47.2	2.0	100	4A3		.16	.54	.69	13.0							1.23	.56
FAGU177	7194	47.2	48.8	1.6	94	4C3		.19	.10	.12	6.0							.22	.55
FAGU177	7195	48.8	50.6	1.8	100	4A34	3.33	.13	2.80	3.60	44.0	1.10	1.55	16.60			6.40	18.15	.56
FAGU177	7196	50.6	51.9	1.3	92	4C3		.13	.06	.09	7.0							.15	.60
FAGU177	7197	51.9	54.7	2.8	82	4A3		.08	.06	.08	10.0							.14	.57
FAGU177	7198	54.7	57.4	2.7	85	4A3		.05	.08	.11	12.0							.19	.58
FAGU177	7199	57.4	60.5	3.1	48	4A3		.03	.05	.06	13.0							.11	.55
FAGA073	7200	61.4	62.9	1.5	100	4AL	3.06	.02	2.50	6.10	41.0	.34	3.68	5.70			8.60	9.38	.71
FAGU059	7201	35.2	37.2	2.0	100	4G4	3.54	.19	6.50	10.00	112.0	.48	.88	19.70			16.50	20.58	.61
FAGU059	7202	37.2	39.2	2.0	100	4G4	4.51	.16	6.50	10.20	101.0	.48	1.32	21.50			16.70	22.82	.61
FAGU059	7203	39.2	41.2	2.0	100	4G4	4.62	.09	6.90	10.20	90.0	.48	1.02	19.50			17.10	20.52	.60
FAGU059	7204	41.2	42.9	1.7	82	4G4	4.71	.18	6.40	10.30	101.0	.69	1.42	21.90			16.70	23.32	.62
FAGU059	7205	42.9	44.6	1.7	100	4G4	4.61	.10	6.90	11.40	115.0	.96	1.47	17.80			18.30	19.27	.62
FAGU059	7206	44.6	46.3	1.7	100	4G4	4.49	.12	7.00	13.40	120.0	.55	3.03	23.80			20.40	26.83	.66
FAGU059	7207	46.3	47.5	1.2	100	4E64	4.77	.35	9.40	13.80	180.0	.27	2.70	25.80			23.20	28.50	.59
FAGU059	7208	47.5	48.5	1.0	90	4E4	4.51	.20	8.40	20.70	138.0	.69	5.72	20.20			29.10	25.92	.71
FAGU059	7209	48.5	50.4	1.9	100	4E4	4.74	.27	7.70	13.60	108.0	.55	3.95	28.20			21.30	32.15	.64
FAGU059	7210	50.4	52.0	1.6	100	4E0	4.61	.28	1.17	.76	30.0	.55	3.31	40.10			1.93	43.41	.39
FAGU059	7211	52.0	53.6	1.6	100	4E0	4.54	.29	.47	.51	21.0	.69	2.77	40.80			.98	43.57	.52
FAGU059	7212	53.6	54.5	.9	100	4E4	4.35	.12	6.50	11.20	107.0	1.71	2.55	25.30			17.70	27.85	.63
FAGU059	7213	101.9	102.9	1.0	100	4A0	3.06	.06	1.26	2.50	23.0	.75	2.47	8.30			3.76	10.77	.66
FAGU059	7214	102.9	104.5	1.6	100	4E4	3.91	.21	2.50	2.80	38.0	.82	2.85	25.20			5.30	28.05	.53

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAO	PB+ZN	PO+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGU059	7215	104.5	105.1	.6	100	4C0	3.31	.21	1.65	2.03	26.0	.89	5.80	13.60		3.68	19.40	.55
FAGU059	7216	105.1	107.3	2.2	100	4A13	3.02	.13	.19	.45	6.0	.55	2.47	8.70		.64	11.17	.70
FAGU059	7217	107.3	109.5	2.2	100	4A13	3.07	.18	.20	.42	8.0	1.17	2.85	9.90		.62	12.75	.68
FAGU059	7218	109.5	110.1	.6	100	4E0	4.04	.16	2.30	2.50	35.0	.75	5.48	22.62		4.80	28.10	.52
FAGU062	7219	.0	1.6	1.6	94	4E4	4.13	.13	6.40	9.60	107.0	1.17	2.13	23.60		16.00	25.73	.60
FAGU062	7220	1.6	3.2	1.6	94	4E4	4.69	.17	4.60	4.60	78.0	1.17	1.93	36.10		9.20	38.03	.50
FAGU062	7221	3.2	4.8	1.6	100	4E4	4.70	.16	5.30	5.50	79.0	1.99	2.74	34.50		10.80	37.24	.51
FAGU062	7222	4.8	6.0	1.2	83	4L14	3.10	.02	1.16	1.92	23.0	3.77	1.07	10.30		3.08	11.37	.62
FAGU062	7223	6.0	8.0	2.0	95	4E4	4.72	.24	6.70	9.30	135.0	2.06	1.30	20.40		16.00	21.70	.58
FAGU062	7224	8.0	9.8	1.8	89	4G4	4.66	.23	5.20	9.20	122.0	1.99	.78	20.90		14.40	21.68	.64
FAGU062	7225	9.8	10.5	.7	100	4G4	4.73	.17	3.70	6.70	89.0	3.02	1.13	24.90		10.40	26.03	.64
FAGU062	7226	10.5	12.0	1.5	100	4E64	4.71	.23	6.20	12.10	111.0	1.65	.95	20.60		18.30	21.55	.66
FAGU062	7227	12.0	13.6	1.6	94	4E4	4.69	.05	5.90	11.50	84.0	1.03	1.44	30.35		17.40	31.79	.66
FAGU062	7228	90.4	92.3	1.9	100	4E4	4.42	.21	5.00	8.20	111.0	1.30	1.41	25.70		13.20	27.11	.62
FAGU062	7229	92.3	94.1	1.8	78	4E4	4.69	.19	7.40	10.60	121.0	1.51	.69	19.60		18.00	20.29	.59
FAGU062	7230	94.1	95.5	1.4	100	4E4	4.66	.22	4.40	7.70	107.0	1.65	1.29	29.10		12.10	30.39	.64
FAGU062	7231	95.5	96.9	1.4	100	4E4	4.61	.23	5.10	8.80	114.0	1.23	1.37	26.90		13.90	28.27	.63
FAGU142	7232	.0	2.1	2.1	62	4E4	4.35	.24	9.10	15.90	183.0	4.46	1.10	18.60		25.00	19.70	.64
FAGU142	7233	2.1	3.0	.9	89	5A9	3.29	.05	1.08	1.79	26.0	.89	1.33	10.70		2.87	12.03	.62
FAGU142	7234	3.0	5.1	2.1	86	4E4	4.14	.07	8.60	11.40	163.0	1.92	1.48	18.00		20.00	19.48	.57
FAGU142	7235	5.1	5.5	.4	100	5A9	3.36	.01	.72	2.04	21.0	.89	1.02	15.10		2.76	16.12	.74
FAGU142	7236	5.5	6.5	1.0	100	4C0	3.58	.02	1.79	2.30	38.0	1.37	1.41	16.80		4.09	18.21	.56
FAGU142	7237	6.5	7.2	.7	100	4A4	3.89	.13	6.20	13.00	142.0	1.92	1.10	16.60		19.20	17.70	.68
FAGU142	7238	7.2	7.9	.7	100	4D0	3.05	.04	3.00	6.50	53.0	.69	1.91	6.40		9.50	8.31	.68
FAGU142	7239	7.9	9.4	1.5	100	4A41	3.31	.01	4.20	7.50	72.0	.82	1.35	9.70		11.70	11.05	.64
FAGU142	7240	9.4	11.0	1.6	100	4A41	3.64	.02	5.00	9.70	96.0	.96	1.34	14.40		14.70	15.74	.66
FAGU142	7241	11.0	11.5	.5	100	5D4	3.28	.01	1.48	3.40	27.0	.55	2.83	10.10		4.88	12.93	.70
FAGU142	7242	16.2	17.0	.8	100	4K1		.01	.21	.15	10.0					.36		.42
FAGU142	7243	21.3	23.4	2.1	95	4K1	3.61	.01	.25	.19	13.0	.41	1.48	18.70		.44	20.18	.43
FAGU142	7244	23.4	24.6	1.2	83	4A4	3.41	.02	3.70	8.50	60.0	.69	1.28	12.00		12.20	13.28	.70
FAGU142	7245	24.6	25.1	.5	100	5D4	3.29	.01	1.94	6.00	33.0	.41	1.55	9.60		7.94	11.15	.76
FAGU142	7246	25.1	25.4	.3	100	4K4	3.15	.10	7.60	18.00	167.0	2.33	1.61	14.60		25.60	16.21	.70
FAGU142	7247	25.4	27.0	1.6	100	4L0	3.30	.01	1.15	2.30	28.0	.34	1.40	6.60		3.45	8.00	.67
FAGU142	7248	27.0	29.0	2.0	100	4K7	3.34	.04	.68	1.10	20.0	.34	7.01	8.60		1.78	15.61	.62
FAGU142	7249	29.0	30.6	1.6	100	4K7		.03	.52	.58	17.0					1.10		.53
FAGU142	7250	30.6	32.4	1.8	100	4K7		.06	.88	1.27	28.0					2.15		.59
FAGU142	7251	32.4	34.4	2.0	90	4K7		.04	.37	.32	16.0					.69		.46
FAGU142	7252	34.4	36.2	1.8	100	4K7		.03	.31	.16	14.0					.47		.34
FAGU142	7253	36.2	38.1	1.9	100	4K0		.04	.21	.40	12.0					.61		.66
FAGU142	7254	38.1	39.6	1.5	100	4K0	3.76	.02	.21	.69	12.0	.21	3.99	20.70		.90	24.69	.77
FAGU142	7255	39.6	39.9	.3	100	4E4	4.20	.06	9.60	18.80	190.0	1.17	1.28	16.60		28.40	17.88	.66
FAGU142	7256	39.9	40.3	.4	100	4D0	3.38	.02	2.14	5.30	45.0	.75	.85	15.20		7.44	16.05	.71
FAGU142	7257	40.3	42.5	2.2	95	4D4	3.38	.03	4.60	10.40	81.0	1.03	1.06	9.40		15.00	10.46	.69
FAGU142	7258	42.5	44.2	1.7	100	4A41	3.27	.03	3.70	9.10	62.0	.89	1.06	8.40		12.80	9.46	.71
FAGU142	7259	44.2	45.9	1.7	100	4A41	3.51	.02	5.50	12.40	95.0	.82	1.26	10.30		17.90	11.56	.69
FAGU142	7260	45.9	46.6	.7	100	4E4	4.61	.09	10.30	24.20	208.0	1.37	1.00	18.00		34.50	19.00	.70
FAGU142	7261	46.6	48.5	1.9	95	4K0	3.98	.01	.68	2.05	20.0	.34	1.45	24.50		2.73	25.95	.75
FAGU142	7262	48.5	50.1	1.6	100	4K4	3.97	.01	1.37	4.30	31.0	.55	1.20	25.20		5.67	26.40	.76
FAGU142	7263	50.1	50.9	.8	100	4E4	4.23	.09	4.90	15.90	120.0	1.30	1.16	21.10		20.80	22.26	.76
FAGU142	7264	50.9	51.4	.5	100	4A4	3.42	.02	4.40	9.50	81.0	.75	.90	12.50		13.90	13.40	.68

DDH	SAMPLE	---DEPTHS---		INT M	REC %	ROCK UNIT	S.G.	CU %	PB %	ZN %	AG G/MT	AU G/MT	PO %	PY %	BAO %	PB+ZN %	PO+PY %	ZN RATIO
		FROM	TO															
FAGU142	7265	51.4	52.9	1.5	100	4E4	4.14	.14	5.60	13.60	100.0	1.78	1.27	22.50		19.20	23.77	.71
FAGU142	7266	52.9	55.1	2.2	95	4E4	4.53	.21	7.60	18.30	160.0	1.78	1.02	21.30		25.90	22.32	.71
FAGU142	7267	55.1	55.5	.4	100	4A4	3.64	.04	7.80	10.00	133.0	1.65	1.48	13.20		17.80	14.68	.56
FAGU142	7268	55.5	55.9	.4	100	5D4*	3.00	.02	.35	.13	8.0	.34	5.08	2.77		.48	7.85	.27
FAGU142	7269	55.9	57.9	2.0	100	4A0	3.38	.07	2.30	2.60	42.0	1.58	1.19	15.80		4.90	16.99	.53
FAGU142	7270	57.9	59.7	1.8	78	4A0	3.52	.03	1.30	3.10	30.0	1.17	2.05	13.60		4.40	15.65	.70
FAGU142	7271	67.0	68.1	1.1	100	4A4	3.31	.05	3.10	5.60	60.0	2.74	1.34	12.40		8.70	13.74	.64
FAGU142	7272	68.1	70.2	2.1	100	4A4	2.99	.02	1.75	3.70	31.0	.69	1.06	1.28		5.45	2.34	.68
FAGU142	7273	96.3	97.6	1.3	100	4C0	3.06	.08	.46	.68	10.0	.41	1.68	7.90		1.14	9.58	.60
FAGU142	7274	97.6	99.5	1.9	100	4A0	2.96	.15	1.28	2.10	24.0	.89	1.25	7.20		3.38	8.45	.62
FAGU142	7275	99.5	101.5	2.0	95	4A0	3.14	.12	.43	1.03	16.0	.89	1.26	12.00		1.46	13.26	.71
FAGU142	7276	101.5	103.6	2.1	100	4A0	3.16	.13	.67	1.61	20.0	1.10	1.23	12.10		2.28	13.33	.71
FAGU142	7277	103.6	105.3	1.7	100	4A0	3.18	.06	2.96	1.72	40.0	1.51	.71	11.90		4.68	12.61	.37
FAGU142	7278	105.3	107.5	2.2	100	4A0	3.20	.07	1.73	1.21	32.0	1.03	.77	11.60		2.94	12.37	.41
FAGU142	7279	107.5	109.4	1.9	100	4A0	3.63	.20	.05	.20	26.0	.82	1.30	24.20		.25	25.50	.80
FAGU142	7280	109.4	111.1	1.7	100	4A0		.26	.06	.30	30.0					.36		.84
FAGU142	7281	111.1	113.1	2.0	100	4A0	3.33	.11	.48	.93	21.0	1.03	1.30	17.40		1.41	18.70	.66
FAGU142	7282	113.1	114.7	1.6	94	4A4	3.16	.03	2.33	3.19	34.0	1.03	1.03	10.40		5.52	11.43	.58
FAGU142	7283	114.7	115.8	1.1	100	4A0	3.38	.10	.06	.20	13.0	.82	1.01	18.30		.26	19.31	.77
FAGU142	7284	115.8	117.0	1.2	100	4A0	3.57	.16	.10	.23	15.0	.69	1.55	23.20		.33	24.75	.70
FAGU142	7285	117.0	119.1	2.1	100	4G4	4.69	.14	4.70	8.10	91.0	2.19	1.01	29.00		12.80	30.01	.63
FAGU142	7286	119.1	121.0	1.9	100	4G0	4.40	.03	1.35	4.00	23.0	.62	.56	17.30		5.35	17.86	.75
FAGU142	7287	121.0	123.0	2.0	100	4G0	4.67	.17	3.00	5.40	64.0	1.30	.66	28.20		8.40	28.86	.64
FAGU142	7288	123.0	125.0	2.0	95	4E4	4.58	.18	5.70	11.00	100.0	1.44	1.76	26.30		16.70	28.06	.66
FAGU142	7289	125.0	127.5	2.5	88	4E46	4.12	.14	3.80	7.80	70.0	1.51	1.50	23.00		11.60	24.50	.67
FAGU142	7290	127.5	128.9	1.4	86	4E4	3.66	.04	3.30	8.10	65.0	1.03	5.01	9.80		11.40	14.81	.71
FAGU110	7291	55.1	57.9	2.8	21	4A4	2.99	.01	1.96	3.50	38.0	.41	1.77	4.23		5.46	6.00	.64
FAGU110	7292	57.9	61.4	3.5	94	4AC	3.34	.06	3.60	4.60	65.0	1.17	2.51	10.40		8.20	12.91	.56
FAGU110	7293	61.4	64.6	3.2	84	4A0	3.22	.08	1.82	2.70	37.0	.62	5.52	8.20		4.52	13.72	.60
FAGU110	7294	64.6	66.7	2.1	67	5A19	2.98	.02	1.06	2.02	12.0	.62	3.12	4.05		3.08	7.17	.66
FAGU114	7295	.0	2.3	2.3	87	4A4	3.33	.02	3.80	8.90	64.0	.82	1.83	9.40		12.70	11.23	.70
FAGU114	7296	2.3	4.6	2.3	91	4A4	3.20	.02	4.20	8.90	70.0	.82	2.26	5.90		13.10	8.16	.68
FAGU114	7297	4.6	6.6	2.0	100	4A4	3.06	.03	3.00	4.80	47.0	.55	2.13	4.21		7.80	6.34	.62
FAGU114	7298	6.6	8.6	2.0	100	4A4	3.32	.02	4.10	5.80	70.0	.89	1.96	9.70		9.90	11.66	.59
FAGU114	7299	8.6	10.2	1.6	62	4A0	3.65	.04	1.12	2.03	36.0	1.23	2.30	20.40		3.15	22.70	.64
FAGU114	7300	10.2	11.8	1.6	100	5A3		.03	.43	.63	11.0					1.06		.59
FAGA073	7301	62.9	64.2	1.3	100	4AL	2.92	.03	2.40	4.30	41.0	.55	2.69	2.44		6.70	5.13	.64
FAGA073	7302	64.6	66.4	1.8	100	4A4	2.90	.04	2.30	4.20	40.0	.55	1.43	1.99		6.50	3.42	.65
FAGA073	7303	66.4	68.3	1.9	95	4A4	2.93	.05	2.20	4.60	35.0	.75	1.02	3.61		6.80	4.63	.68
FAGA073	7304	68.3	70.1	1.8	100	4A4	2.79	.09	3.20	5.00	51.0	.89	1.79	6.07		8.20	7.86	.61
FAGA073	7305	70.1	71.9	1.8	100	4A4	2.94	.04	2.40	5.20	40.0	.89	1.09	3.64		7.60	4.73	.68
FAGA073	7306	71.9	73.8	1.9	95	4A4	2.93	.03	1.90	5.40	39.0	.41	1.05	2.84		7.30	3.89	.74
FAGA073	7307	73.8	75.6	1.8	100	4A0	3.09	.06	1.15	2.80	23.0	.48	3.53	6.40		3.95	9.93	.71
FAGA073	7308	299.1	301.3	2.2	100	4AL	3.13	.07	1.85	4.30	31.0	.55	2.93	5.90		6.15	8.83	.70
FAGA073	7309	301.3	302.8	1.5	100	4G4#	4.22	.04	6.40	8.10	97.0	1.44	1.29	15.50		14.50	16.79	.56
FAGA073	7310	302.8	304.5	1.7	76	4ELC	3.79	.16	4.20	5.80	65.0	1.85	2.77	20.50		10.00	23.27	.58
FAGU087	7311	55.0	56.6	1.6	75	4A10	3.49	.11	1.31	3.60	33.0	.55	2.22	14.20		4.91	16.42	.73
FAGU138	7312	2.6	3.9	1.3	85	5CD		.02	.88	1.72	16.0					2.60		.66
FAGU138	7313	6.2	7.1	.9	100	4L14		.02	2.40	2.90	37.0					5.30		.55
FAGU138	7314	31.6	33.3	1.7	94	4A1	2.96	.04	2.10	1.51	27.0	.82	2.01	3.93		3.61	5.94	.42

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAG	PB+ZN	PO+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGU138	7315	33.3	34.9	1.6	100	4A1	2.93	.06	.60	.43	9.0	.96	.86	5.99		1.03	6.85	.42
FAGU138	7316	34.9	36.5	1.6	94	4A1	3.03	.10	1.32	2.40	22.0	1.10	1.08	6.40		3.72	7.48	.65
FAGU138	7317	36.5	38.0	1.5	100	4A14	2.94	.05	1.82	4.30	26.0	1.10	1.06	3.27		6.12	4.33	.70
FAGU138	7318	38.0	39.5	1.5	100	4A14	2.95	.06	4.00	2.70	56.0	.89	.96	2.66		6.70	3.62	.40
FAGU138	7319	39.5	41.7	2.2	100	4A1	2.96	.09	1.58	.70	25.0	1.10	1.59	5.56		2.28	7.15	.31
FAGU138	7320	41.7	43.9	2.2	91	4A1	2.86	.05	.23	.44	5.0	.82	.84	3.60		.67	4.44	.66
FAGU138	7321	43.9	46.0	2.1	90	4A1	2.94	.03	1.04	.60	15.0	.69	.94	3.56		1.64	4.50	.37
FAGU138	7322	46.0	47.7	1.7	100	4L04	2.98	.04	4.80	1.00	53.0	.96	1.16	2.59		5.80	3.75	.17
FAGU138	7323	47.7	49.4	1.7	100	4L04	2.87	.02	1.26	1.33	19.0	.55	.97	.93		2.59	1.90	.51
FAGU138	7324	49.4	51.1	1.7	100	4L04	2.91	.02	1.18	1.91	21.0	.62	1.11	.79		3.09	1.90	.62
FAGU138	7325	51.1	52.7	1.6	88	4L04	2.89	.02	.60	1.41	9.0	.41	2.01	.94		2.01	2.95	.70
FAGU138	7326	52.7	54.8	2.1	100	4L14	3.05	.04	2.40	.68	29.0	.82	1.86	3.39		3.08	5.25	.22
FAGU138	7327	54.8	56.8	2.0	100	4L14	3.04	.04	1.18	.90	18.0	.75	1.20	4.38		2.08	5.58	.43
FAGU138	7328	56.8	59.1	2.3	96	4A1	2.92	.06	1.61	2.60	30.0	.96	.73	3.92		4.21	4.65	.62
FAGU138	7329	59.1	61.0	1.9	100	4L14	2.96	.06	1.10	1.15	22.0	.89	2.08	3.39		2.25	5.47	.51
FAGU138	7330	61.0	63.0	2.0	100	4L1	2.85	.03	.49	.57	8.0	.41	2.81	1.90		1.06	4.71	.54
FAGU138	7331	76.3	77.0	.7	100	4L1\$	2.97	.04	.42	.96	10.0	.21	2.09	14.10		1.38	16.19	.70
FAGU138	7332	77.0	78.9	1.9	100	4A1	3.14	.06	1.54	2.70	29.0	.96	.78	10.10		4.24	10.88	.64
FAGU138	7333	78.9	80.3	1.4	100	4A3	3.55	.13	.07	.16	28.0	1.17	1.03	21.70		.23	22.73	.70
FAGU138	7334	80.3	81.7	1.4	100	4A3	3.15	.05	.80	.68	19.0	4.10	.73	11.70		1.48	12.43	.46
FAGU138	7335	81.7	83.5	1.8	100	4A14	3.02	.06	2.70	4.30	43.0	.82	1.02	4.28		7.00	5.30	.61
FAGU138	7336	83.5	84.6	1.1	100	4A13	3.04	.06	.31	.49	12.0	.75	.92	9.60		.80	10.52	.61
FAGU138	7337	107.7	108.5	.8	100	4E1	3.31	.03	4.70	9.00	64.0	1.17	1.42	18.00		13.70	19.42	.66
FAGU138	7338	108.5	110.2	1.7	100	4A3	3.17	.07	.67	.97	17.0	.75	.82	13.40		1.64	14.22	.59
FAGU138	7339	110.2	112.0	1.8	100	4A3	3.21	.07	1.02	1.86	21.0	.69	.83	12.00		2.88	12.83	.65
FAGU138	7340	112.7	114.0	1.3	62	4A1	2.79	.06	1.03	2.40	19.0	.41	1.42	9.70		3.43	11.12	.70
FAGU138	7341	114.0	115.8	1.8	61	4A1	2.98	.08	.93	1.54	16.0	.55	1.12	5.80		2.47	6.92	.62
FAGU138	7342	115.8	117.6	1.8	78	4A1	2.91	.05	1.25	2.16	17.0	.41	1.83	3.62		3.41	5.45	.63
FAGU167	7343	.9	1.8	.9	100	4CE		.25	.21	.75	9.0					.96		.78
FAGU167	7344	1.8	4.0	2.2	86	4CE	3.54	.28	.28	1.03	19.0	.96	2.68	19.60		1.31	22.28	.79
FAGU167	7345	4.0	6.1	2.1	100	4CE	3.61	.28	1.37	2.30	33.0	1.99	2.98	19.60		3.67	22.58	.63
FAGU167	7346	11.6	12.8	1.2	100	4H14	3.50	.26	5.10	6.00	84.0	1.51	9.50	9.25		11.10	18.75	.54
FAGU167	7347	32.2	34.4	2.2	59	4G4	4.26	.15	5.00	8.60	76.0	.75	.91	21.80		13.60	22.71	.63
FAGU167	7348	34.4	36.6	2.2	95	4G4	4.83	.12	4.40	6.60	68.0	1.03	.62	27.00		11.00	27.62	.60
FAGU167	7349	36.6	38.3	1.7	100	4E46	4.71	.14	3.90	4.60	60.0	1.92	.72	37.80		8.50	38.52	.54
FAGU167	7350	38.3	40.0	1.7	88	4E46	4.57	.20	4.40	6.60	87.0	1.44	.67	28.50		11.00	29.17	.60
FAGU167	7351	40.0	42.1	2.1	100	4G4	4.54	.11	4.20	7.10	77.0	.96	.51	18.40		11.30	18.91	.63
FAGU167	7352	42.1	42.6	.5	100	5A16	3.33	.10	2.80	3.80	60.0	.96	.82	10.60		6.60	11.42	.58
FAGU167	7353	42.6	44.3	1.7	100	4G4	4.51	.13	5.70	10.70	102.0	1.44	1.14	16.10		16.40	17.24	.65
FAGU167	7354	44.3	45.7	1.4	100	4E46	4.46	.24	5.10	7.20	79.0	1.65	1.78	33.20		12.30	34.98	.59
FAGU167	7355	45.7	46.2	.5	100	4G4	4.53	.11	8.10	12.70	139.0	1.10	1.37	19.20		20.80	20.57	.61
FAGU167	7356	46.2	48.1	1.9	79	4E4	4.29	.11	9.00	14.10	149.0	1.58	2.30	23.90		23.10	26.20	.61
FAGU167	7357	48.1	49.2	1.1	82	4G4	4.26	.24	6.10	12.60	101.0	1.85	1.10	20.10		18.70	21.20	.67
FAGU165	7358	.0	2.3	2.3	39	4A34	3.46	.24	3.30	4.90	47.0	1.99	1.72	18.00		8.20	19.72	.60
FAGU165	7359	2.3	4.4	2.1	86	4A3	3.35	.21	1.48	2.05	24.0	.89	1.76	18.80		3.53	20.56	.58
FAGU165	7360	4.4	6.1	1.7	100	4C0	3.46	.25	.13	.75	10.0	.69	2.19	22.40		.88	24.59	.85
FAGU165	7361	6.1	7.6	1.5	93	4C0	3.41	.26	.08	.53	11.0	.55	2.37	21.40		.61	23.77	.87
FAGU165	7362	7.6	9.5	1.9	95	4C0	3.57	.27	.91	1.40	30.0	1.03	2.15	24.50		2.31	26.65	.61
FAGU165	7363	18.3	20.7	2.4	79	4E1		.27	.67	.82	27.0					1.49		.55
FAGU165	7364	20.7	22.9	2.2	95	4E1		.35	.14	.65	31.0					.79		.82

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAO	PB+ZN	PO+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGU165	7365	22.9	25.3	2.4	92	4C3	3.56	.34	.12	1.17	14.0	.62	3.49	20.40		1.29	23.89	.91
FAGU165	7366	25.3	27.4	2.1	95	4C5	3.62	.22	1.57	1.63	46.0	1.10	1.47	22.70		3.20	24.17	.51
FAGU165	7367	27.4	30.1	2.7	81	4C3		.51	.12	.72	20.0					.84		.86
FAGU165	7368	30.1	32.5	2.4	92	4C3		.22	.07	.42	12.0					.49		.86
FAGU165	7369	32.5	33.1	.6	100	4C0	3.08	1.09	.03	.34	30.0	1.99	4.25	13.30		.37	17.55	.92
FAGU165	7370	33.1	35.0	1.9	100	4C3	3.64	.51	.07	.53	17.0	.75	4.25	22.10		.60	26.35	.88
FAGU165	7371	35.0	36.9	1.9	100	4E1	3.99	.43	1.25	2.02	37.0	1.30	4.53	30.80		3.27	35.33	.62
FAGU165	7372	36.9	39.6	2.7	85	4E1	4.49	.31	1.46	2.60	36.0	1.58	2.32	37.70		4.06	40.02	.64
FAGU165	7373	39.6	41.7	2.1	95	4E1	4.21	.32	1.00	1.09	31.0	1.78	2.19	36.00		2.09	38.19	.52
FAGU128	7374	.0	3.6	3.6	11	4A0	3.02	.04	1.92	2.20	27.0	.82	2.00	6.10		4.12	8.10	.53
FAGU128	7375	3.6	5.0	1.4	100	4A4	3.24	.08	2.95	4.30	55.0	1.10	.99	10.60		7.25	11.59	.59
FAGU128	7376	5.0	6.5	1.5	100	4A4	3.41	.09	2.96	5.67	55.0	.89	.91	14.50		8.63	15.41	.66
FAGU128	7377	6.5	8.0	1.5	100	4A4	3.10	.05	1.92	4.00	32.0	.69	.87	8.50		5.92	9.37	.68
FAGU128	7378	8.0	9.5	1.5	100	4A4	3.04	.07	2.18	3.80	37.0	.89	.76	6.60		5.98	7.36	.64
FAGU128	7379	9.5	11.1	1.6	100	4A4	3.38	.06	2.53	4.10	40.0	.89	.87	4.59		6.63	5.46	.62
FAGU128	7380	11.1	13.3	2.2	100	4A0	2.89	.03	1.87	3.10	25.0	.55	.75	3.45		4.97	4.20	.62
FAGU128	7381	13.3	14.8	1.5	80	4A14	2.95	.03	1.89	4.00	26.0	.82	.88	3.22		5.89	4.10	.68
FAGU128	7382	14.8	16.7	1.9	100	4A14	3.21	.03	1.40	4.40	30.0	.82	.76	10.30		5.80	11.06	.76
FAGU128	7383	16.7	18.7	2.0	75	4D4S	3.80	.05	7.78	9.10	128.0	1.65	1.20	17.80		16.88	19.00	.54
FAGU128	7384	18.7	19.6	.9	100	4D0	3.31	.06	4.53	3.80	53.0	1.37	1.19	11.00		8.33	12.19	.46
FAGU128	7385	24.5	26.5	2.0	95	4A14	3.67	.16	2.75	3.60	48.0	1.78	18.90	1.77		6.35	20.67	.57
FAGU128	7386	67.5	67.8	.3	100	4A4		.06	4.64	8.40	92.0					13.04		.64
FAGU128	7387	69.7	70.6	.9	100	4D4	3.65	.10	6.42	10.20	97.0	1.51	1.58	15.30		16.62	16.88	.61
FAGU128	7388	70.6	72.0	1.4	100	4A14	3.79	.11	4.32	4.50	76.0	2.19	1.21	21.30		8.82	22.51	.51
FAGU128	7389	72.0	74.7	2.7	93	4D4E	3.79	.10	7.26	9.60	103.0	2.06	1.57	16.70		16.86	18.27	.57
FAGU128	7390	74.7	76.3	1.6	100	4D4	3.68	.09	6.21	10.10	90.0	1.85	1.82	14.70		16.31	16.52	.62
FAGU128	7391	76.3	77.6	1.3	100	4D4@	3.54	.08	5.47	9.90	87.0	1.65	1.91	12.20		15.37	14.11	.64
FAGU128	7392	77.6	78.9	1.3	77	5A0	3.05	.03	3.06	3.70	48.0	.41	2.72	4.10		6.76	6.82	.55
FAGU128	7393	79.4	81.6	2.2	100	4GE4	4.64	.09	5.26	10.70	92.0	1.37	.60	19.50		15.96	20.10	.67
FAGU128	7394	81.6	82.5	.9	89	4G4@	4.63	.08	5.47	10.40	100.0	1.30	1.04	26.00		15.87	27.04	.66
FAGU128	7395	82.5	83.8	1.3	100	4G4	4.66	.11	6.84	10.50	102.0	1.65	.73	18.65		17.34	19.38	.61
FAGU134	7396	5.9	6.7	.8	100	4L4	2.90	.10	.67	1.45	12.0	.41	2.70	3.23		2.12	5.93	.68
FAGU134	7397	6.7	8.0	1.3	85	5A19	2.97	.03	1.12	.70	12.0	.21	3.08	3.15		1.82	6.23	.38
FAGU134	7398	19.3	20.6	1.3	100	4L0	3.13	.02	.14	.44	1.0	.27	4.37	1.36		.58	5.73	.76
FAGU134	7399	29.0	29.8	.8	100	4D0	3.34	.04	4.85	2.90	84.0	.96	1.06	4.97		7.75	6.03	.37
FAGU134	7400	29.8	31.8	2.0	100	4A1	3.05	.06	2.64	1.17	37.0	1.03	.65	3.60		3.81	4.25	.31
FAGU114	7401	16.4	18.4	2.0	100	4A4	3.41	.05	4.30	9.00	76.0	.75	3.67	7.61		13.30	11.28	.68
FAGU114	7402	18.4	20.4	2.0	95	4A4	3.59	.07	2.90	5.80	58.0	.96	1.71	14.70		8.70	16.41	.67
FAGU114	7403	20.4	22.9	2.5	100	4A4	3.41	.08	1.87	4.10	45.0	.89	1.12	18.26		5.97	19.38	.69
FAGU114	7404	24.4	26.4	2.0	100	4A4	3.41	.05	1.88	4.60	44.0	.89	1.04	14.10		6.48	15.14	.71
FAGU114	7405	26.4	28.4	2.0	100	4A4	3.45	.03	1.96	4.20	42.0	1.03	1.11	13.20		6.16	14.31	.68
FAGU114	7406	28.4	30.4	2.0	100	4A0	3.01	.01	.81	1.79	22.0	.21	2.48	4.54		2.60	7.02	.69
FAGU114	7407	30.4	32.4	2.0	100	4A4	3.47	.03	1.56	3.70	38.0	.96	1.15	14.00		5.26	15.15	.70
FAGU114	7408	32.4	34.4	2.0	100	4A4	3.49	.02	2.93	5.10	56.0	1.78	1.77	13.60		8.03	15.37	.64
FAGU114	7409	34.4	36.4	2.0	100	4A4	3.84	.04	3.84	6.80	70.0	1.17	2.61	16.30		10.64	18.91	.64
FAGU114	7410	36.4	38.4	2.0	100	4A4	3.57	.05	3.17	4.70	60.0	1.10	.91	18.20		7.87	19.11	.60
FAGU114	7411	38.4	40.4	2.0	50	4D0	3.18	.08	2.77	4.20	52.0	.69	2.33	8.10		6.97	10.43	.60
FAGU114	7412	40.4	42.4	2.0	95	4D0	2.97	.05	1.73	4.10	33.0	.48	1.01	2.64		5.83	3.65	.70
FAGU114	7413	42.4	44.4	2.0	100	4D0	2.86	.05	1.59	4.10	31.0	.34	.69	2.48		5.69	3.17	.72
FAGU114	7414	44.4	45.7	1.3	100	4C0	3.02	.09	1.86	3.10	29.0	.48	.72	6.30		4.96	7.02	.63

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAO	PB+ZN	PO+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGU061	7415	1.2	3.2	2.0	95	4A14	3.52	.05	3.10	5.30	38.0	.82	1.50	7.50		8.40	9.00	.63
FAGU061	7416	3.2	5.2	2.0	100	4A14	3.11	.07	2.40	3.80	32.0	1.03	.95	6.50		6.20	7.45	.61
FAGU061	7417	5.2	7.2	2.0	100	4A14	3.16	.05	3.60	5.20	48.0	.82	.94	5.90		8.80	6.84	.59
FAGU061	7418	7.2	9.2	2.0	100	4A14	3.33	.06	3.80	5.10	62.0	.96	1.01	11.50		8.90	12.51	.57
FAGU061	7419	9.2	11.3	2.1	100	4A30	3.66	.17	.31	1.03	13.0	.75	1.92	23.70		1.34	25.62	.77
FAGU061	7420	11.3	13.4	2.1	100	4A30	3.72	.24	.65	.35	35.0	1.51	1.70	26.50		1.00	28.20	.35
FAGU061	7421	13.4	15.5	2.1	100	4A30	3.50	.11	.82	1.55	31.0	.82	1.57	21.00		2.37	22.57	.65
FAGU061	7422	15.5	16.9	1.4	100	4A14	3.08	.06	2.03	4.20	38.0	.69	.87	5.95		6.23	6.82	.67
FAGU061	7423	16.9	18.4	1.5	100	4A13	3.45	.16	.46	.55	29.0	.69	1.21	21.30		1.01	22.51	.54
FAGU061	7424	18.4	20.4	2.0	90	4E0	3.72	.20	.14	.38	15.0	1.10	2.02	26.70		.52	28.72	.73
FAGU061	7425	20.4	22.4	2.0	100	4E0	3.60	.19	.08	.32	11.0	.69	1.69	23.70		.40	25.39	.80
FAGU061	7426	22.4	24.3	1.9	100	4E0	3.67	.33	.11	.30	13.0	.89	2.49	26.30		.41	28.79	.73
FAGU061	7427	24.3	25.1	.8	88	4E4	4.49	.20	8.30	10.00	141.0	1.65	2.71	25.50		18.30	28.21	.55
FAGU061	7428	25.1	25.8	.7	100	4E14	3.82	.24	3.30	3.20	58.0	1.78	1.85	24.10		6.50	25.95	.49
FAGU061	7429	25.8	27.4	1.6	100	4E74	4.85	.15	9.70	7.10	147.0	1.44	4.60	29.00		16.80	33.60	.42
FAGU061	7430	27.4	29.0	1.6	100	4E74	4.85	.14	8.60	4.40	137.0	1.58	4.80	30.40		13.00	35.20	.34
FAGU061	7431	29.0	30.0	1.0	100	4E0		.34	.77	.35	28.0					1.12		.31
FAGU061	7432	30.0	30.6	.6	100	4G4	4.83	.16	7.60	9.30	115.0	1.78	2.00	22.70		16.90	24.70	.55
FAGU061	7433	30.6	32.8	2.2	86	4E4	4.18	.20	5.90	7.80	100.0	1.78	1.83	23.80		13.70	25.63	.57
FAGU061	7434	55.8	56.3	.5	100	4G4	4.20	.15	5.00	7.40	92.0	1.44	1.57	17.30		12.40	18.87	.60
FAGU061	7435	59.9	60.9	1.0	100	4G4	4.46	.18	6.80	10.70	136.0	2.06	1.72	11.30		17.50	13.02	.61
FAGU061	7436	87.4	89.1	1.7	100	4E1	4.39	.10	2.10	2.50	45.0	1.10	1.77	32.50		4.60	34.27	.54
FAGU061	7437	89.1	90.8	1.7	88	4E1	4.24	.16	2.20	2.50	37.0	1.17	1.59	29.80		4.70	31.39	.53
FAGU061	7438	90.8	91.3	.5	100	5A\$	3.17	.16	1.14	1.15	24.0	.55	2.12	9.90		2.29	12.02	.50
FAGU061	7439	91.3	91.7	.4	100	4A1	2.95	.03	1.12	2.30	23.0	.62	2.30	4.70		3.42	7.00	.67
FAGU061	7440	91.7	92.8	1.1	100	4H1	3.99	.11	.99	1.40	24.0	.69	2.99	31.60		2.39	34.59	.59
FAGU061	7441	92.8	96.7	3.9	100	4A1		.08	.56	.74	14.0					1.30		.57
FAGU061	7442	112.2	113.7	1.5	100	4D4	3.62	.10	6.90	14.50	115.0	1.44	4.44	11.25		21.40	15.69	.68
FAGU061	7443	113.7	115.2	1.5	100	4D4	3.55	.10	7.00	14.70	121.0	1.65	2.19	9.90		21.70	12.09	.68
FAGU060	7444	1.1	2.7	1.6	94	4A14	4.49	.04	3.20	4.10	35.0	.96	1.29	7.10		7.30	8.39	.56
FAGU060	7445	2.7	4.3	1.6	100	4A14	3.29	.05	2.90	5.00	33.0	1.10	.82	6.60		7.90	7.42	.63
FAGU060	7446	4.3	6.5	2.2	100	4A14	3.12	.05	2.70	3.40	33.0	1.03	1.19	5.98		6.10	7.17	.56
FAGU060	7447	6.5	8.6	2.1	100	4A14	3.14	.04	3.20	3.70	40.0	1.23	.69	7.30		6.90	7.99	.54
FAGU060	7448	8.6	10.7	2.1	100	4A10	2.92	.02	.53	1.95	12.0	.62	1.08	2.53		2.48	3.61	.79
FAGU060	7449	10.7	12.2	1.5	53	4A14	3.08	.03	3.80	4.10	49.0	1.10	.64	4.80		7.90	5.44	.52
FAGU060	7450	12.2	14.4	2.2	68	4A10	2.54	.04	1.18	.85	19.0	1.23	.70	7.20		2.03	7.90	.42
FAGU060	7451	14.4	16.6	2.2	100	4A10	2.96	.06	1.14	1.30	22.0	1.37	1.15	6.70		2.44	7.85	.53
FAGU060	7452	16.6	18.7	2.1	100	4A10	3.12	.10	1.58	2.02	31.0	1.03	2.56	9.60		3.60	12.16	.56
FAGU060	7453	18.7	20.8	2.1	100	4A13	2.94	.08	1.08	1.21	24.0	.82	.87	7.74		2.29	8.61	.53
FAGU060	7454	20.8	22.8	2.0	100	4A13	3.04	.08	.84	1.24	19.0	.96	1.40	10.30		2.08	11.70	.60
FAGU060	7455	22.8	24.0	1.2	100	4A14	3.36	.13	2.02	3.90	39.0	1.23	3.00	13.50		5.92	16.50	.66
FAGU060	7456	24.0	25.8	1.8	100	4A10	3.18	.12	1.58	2.03	28.0	1.23	1.08	12.60		3.61	13.68	.56
FAGU060	7457	25.8	27.6	1.8	100	4A14	3.05	.08	2.63	3.50	42.0	1.10	1.64	6.40		6.13	8.04	.57
FAGU060	7458	27.6	28.1	.5	100	4A30	3.50	.19	.35	.63	16.0	.89	2.99	21.20		.98	24.19	.64
FAGU060	7459	28.1	29.2	1.1	91	4E0	4.02	.34	.16	1.41	14.0	1.10	1.72	33.50		1.57	35.22	.90
FAGU060	7460	29.2	29.9	.7	100	4E*4	4.20	.23	5.50	9.30	91.0	1.58	1.68	25.20		14.80	26.88	.63
FAGU060	7461	29.9	31.5	1.6	81	4A10	3.37	.17	.46	1.20	18.0	.96	2.25	19.70		1.66	21.95	.72
FAGU060	7462	31.5	32.5	1.0	90	4E4	4.63	.14	9.00	9.10	143.0	1.99	1.22	29.10		18.10	30.32	.50
FAGU060	7463	32.5	34.1	1.6	100	4G4	4.59	.18	4.70	7.80	91.0	.89	1.43	20.31		12.50	21.74	.62
FAGU060	7464	42.8	44.0	1.2	100	4E64	4.53	.13	4.20	5.40	61.0	1.37	1.21	30.10		9.60	31.31	.56

DDH	SAMPLE	---DEPTHS---		INT M	REC %	ROCK UNIT	S.G.	CU %	PB %	ZN %	AG G/MT	AU G/MT	PO %	PY %	BAC %	PB+ZN %	PC+PY %	ZN RATIO
		FROM	TO															
FAGU060	7465	56.4	56.8	.4	100	4G#4	4.01	.13	6.00	10.70	107.0	1.17	4.08	16.50		16.70	20.58	.64
FAGU060	7466	59.4	60.7	1.3	92	4E#4	4.02	.05	2.70	3.80	74.0	1.10	.69	18.80		6.50	19.49	.58
FAGU060	7467	60.7	62.0	1.3	38	4E#4	4.13	.04	6.10	10.70	102.0	.62	3.73	14.10		16.80	17.83	.64
FAGU060	7468	96.0	97.0	1.0	100	4A0	2.97	.07	1.20	2.50	23.0	.55	2.57	3.82		3.70	6.39	.68
FAGU060	7469	105.5	106.1	.6	100	4D4	3.67	.11	8.60	13.50	152.0	1.99	4.32	7.90		22.10	12.22	.61
FAGU060	7470	106.1	107.9	1.8	100	4E4	4.39	.30	3.30	5.00	67.0	1.92	2.54	30.30		8.30	32.84	.60
FAGU060	7471	107.9	109.7	1.8	100	4E4	4.01	.37	4.30	7.40	82.0	1.78	3.66	20.90		11.70	24.56	.63
FAGU060	7472	109.7	111.5	1.8	100	4E0	4.04	.59	.86	2.50	31.0	1.44	3.06	27.50		3.36	30.56	.74
FAGU060	7473	111.5	112.3	.8	100	4E14	3.56	.18	4.40	7.10	82.0	1.51	2.09	17.18		11.50	19.27	.62
FAGA155	7474	41.8	43.6	1.8	89	4A41	3.14	.09	1.96	3.90	41.0	.62	.79	9.50		5.86	10.29	.67
FAGA155	7475	43.6	44.9	1.3	100	4A41	3.08	.02	2.83	5.60	47.0	.75	1.10	5.60		8.43	6.70	.66
FAGA155	7476	44.9	45.6	.7	86	4D4	3.20	.05	4.00	9.60	71.0	.55	3.31	5.10		13.60	8.41	.71
FAGA155	7477	45.6	47.7	2.1	100	4A43	3.26	.06	2.82	5.80	48.0	.75	.96	9.70		8.62	10.66	.67
FAGA155	7478	47.7	49.4	1.7	100	4A43	3.23	.04	3.50	6.20	56.0	1.10	1.12	8.10		9.70	9.22	.64
FAGA155	7479	49.4	51.5	2.1	100	4A43	3.14	.04	2.65	5.30	43.0	1.37	1.12	6.80		7.95	7.92	.67
FAGA155	7480	51.5	52.9	1.4	100	4A43	3.10	.03	2.50	6.10	44.0	.89	.95	6.10		8.60	7.05	.71
FAGA155	7481	52.9	53.3	.4	100	4E4	4.08	.02	10.10	1.98	168.0	2.06	3.28	14.56		12.08	17.84	.16
FAGA155	7482	53.3	54.1	.8	100	4A31	3.34	.04	3.70	7.40	61.0	.89	1.77	9.30		11.10	11.07	.67
FAGA155	7483	56.9	57.7	.8	88	4D0	3.55	.12	2.80	6.80	56.0	.82	4.36	13.10		9.60	17.46	.71
FAGA155	7484	57.7	59.1	1.4	100	4D4	3.06	.05	4.80	6.20	79.0	.75	2.65	2.82		11.00	5.47	.56
FAGA155	7485	59.1	60.7	1.6	94	4D4	3.04	.04	3.60	6.60	62.0	.89	2.16	2.18		10.20	4.34	.65
FAGA155	7486	60.7	62.3	1.6	100	4D0	3.01	.04	2.40	3.70	41.0	.62	3.81	2.58		6.10	6.39	.61
FAGA155	7487	62.3	63.1	.8	100	4A10	3.04	.04	2.00	2.70	35.0	.89	.79	6.80		4.70	7.59	.57
FAGA155	7488	63.1	64.0	.9	100	4A14	3.27	.05	2.50	3.80	45.0	1.03	.98	11.00		6.30	11.98	.60
FAGA155	7489	64.0	66.0	2.0	100	4A10	3.04	.04	1.20	1.24	22.0	.69	.75	7.10		2.44	7.85	.51
FAGA155	7490	66.0	67.8	1.8	100	4A30	3.33	.06	.87	1.55	22.0	1.10	1.33	20.90		2.42	22.23	.64
FAGA155	7491	67.8	69.5	1.7	100	4A0	3.06	.05	.82	1.82	24.0	.55	.81	11.80		2.64	12.61	.69
FAGA155	7492	69.5	71.2	1.7	100	4A4	3.03	.04	3.40	4.50	57.0	.89	1.05	5.13		7.90	6.18	.57
FAGA155	7493	74.9	75.9	1.0	100	4A0		.04	.48	.63	15.0					1.11		.57
FAGA155	7494	75.9	76.6	.7	86	5D4*		.02	.07	.44	1.0					.51		.86
FAGA155	7495	76.6	77.4	.8	100	4D0	3.28	.05	3.81	2.06	41.0	2.13	1.58	10.80		5.87	12.38	.35
FAGA155	7496	77.4	79.6	2.2	100	4E41	3.03	.09	7.20	12.60	116.0	1.71	1.69	15.50		19.80	17.19	.64
FAGA155	7497	79.6	80.5	.9	100	4A4	3.41	.05	5.50	6.90	84.0	1.71	2.41	10.30		12.40	12.71	.56
FAGA155	7498	80.5	81.7	1.2	100	4E4	3.92	.05	10.70	17.20	182.0	2.54	2.50	12.50		27.90	15.00	.62
FAGA155	7499	81.7	83.9	2.2	100	3G0	2.98	.01	.50	.64	11.0	.27	3.57	3.33		1.14	6.90	.56
FAGA155	7500	83.9	84.9	1.0	100	4A1	3.94	.02	1.86	4.00	43.0	2.74	2.17	9.00		5.86	11.17	.68
FAGA155	7501	84.9	85.6	.7	100	5D4@	2.99	.02	.16	1.86	2.0	.48	7.83	1.62		2.02	9.45	.92
FAGA155	7502	85.6	87.2	1.6	100	4A4	3.25	.03	2.75	6.30	53.0	.69	4.72	7.70		9.05	12.42	.70
FAGU130	7503	.0	2.2	2.2	45	4L14	2.98	.04	2.80	1.60	45.0	.69	1.12	3.02		4.40	4.14	.36
FAGU130	7504	8.5	10.0	1.5	100	4A14	3.07	.04	1.81	3.90	36.0	.69	2.67	6.20		5.71	8.87	.68
FAGU130	7505	10.0	11.0	1.0	100	4A14	3.11	.04	2.99	5.10	47.0	1.03	1.90	6.70		8.09	8.60	.63
FAGU130	7506	18.2	19.5	1.3	100	4D0	3.12	.02	2.84	5.60	43.0	1.37	1.22	6.70		8.44	7.92	.66
FAGU130	7507	19.5	21.0	1.5	100	4A14	3.02	.03	4.00	7.70	68.0	1.03	1.43	9.00		11.70	10.43	.66
FAGU130	7508	21.0	22.9	1.9	89	4A14	3.34	.09	3.80	7.30	63.0	1.37	1.86	11.00		11.10	12.86	.66
FAGU130	7509	22.9	24.3	1.4	100	4A14	3.12	.09	2.53	5.00	47.0	1.03	1.32	7.40		7.53	8.72	.66
FAGU130	7510	24.3	24.9	.6	100	5C*3	3.02	.01	.08	.13	2.0	.96	4.90	.97		.21	5.87	.62
FAGU130	7511	24.9	26.9	2.0	100	4L14	3.03	.03	2.33	2.88	35.0	.82	1.24	2.54		5.21	3.78	.55
FAGU130	7512	26.9	28.1	1.2	100	4L14	3.10	.04	4.60	3.70	74.0	1.17	.81	6.10		8.30	6.91	.45
FAGU130	7513	28.1	29.5	1.4	100	4L14	3.02	.03	3.00	3.60	49.0	.96	.73	4.54		6.60	5.27	.55
FAGU130	7514	29.5	31.0	1.5	100	4L14	3.01	.04	1.49	2.70	27.0	.96	.72	5.84		4.19	6.56	.64







DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAO	PB+ZN	PO+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGU124	7665	18.2	19.7	1.5	87	4D4	3.42	.04	5.40	7.80	82.0	1.10	1.35	11.22		13.20	12.57	.59
FAGU124	7666	19.7	20.8	1.1	100	4A3	3.41	.08	.97	2.60	21.0	1.03	1.72	14.73		3.57	16.45	.73
FAGU124	7667	25.9	27.9	2.0	90	4C2	3.58	.18	1.65	3.20	43.0	1.99	1.69	18.07		4.85	19.76	.66
FAGU124	7668	27.9	29.5	1.6	94	4D2	3.56	.16	2.70	4.30	63.0	1.92	1.47	17.34		7.00	18.81	.61
FAGU124	7669	29.5	30.4	.9	100	4L0	2.94	.03	.09	.21	5.0	.48	1.66	4.00		.30	5.66	.70
FAGU124	7670	30.4	32.7	2.3	100	4A3	3.40	.09	1.46	1.70	40.0	1.65	1.32	15.03		3.16	16.35	.54
FAGU124	7671	32.7	34.1	1.4	100	4A34	3.53	.11	2.60	3.60	51.0	2.67	2.50	13.76		6.20	16.26	.58
FAGU124	7672	34.1	34.8	.7	100	4D0	3.01	.09	3.20	5.90	59.0	2.33	1.90	20.32		9.10	22.22	.65
FAGU124	7673	34.8	37.5	2.7	100	4A14	3.54	.13	3.30	4.30	59.0	2.61	1.41	17.86		7.60	19.27	.57
FAGU124	7674	38.7	39.6	.9	100	4D24	3.31	.20	2.70	8.00	36.0	1.23	4.04	6.92		10.70	10.96	.75
FAGU124	7675	39.6	42.3	2.7	100	4D4	4.40	.10	15.50	27.00	254.0	1.78	1.90	10.00		42.50	11.90	.64
FAGU124	7676	42.3	43.0	.7	100	4A0	3.03	.02	1.17	.27	22.0	.48	.87	3.37		1.44	4.24	.19
FAGU124	7677	44.9	46.5	1.6	100	4K14	3.96	.10	5.60	17.70	108.0	.82	5.00	11.73		23.30	16.73	.76
FAGU124	7678	46.5	47.5	1.0	100	4AL4	3.24	.09	2.60	3.70	41.0	1.10	2.60	8.56		6.30	11.16	.59
FAGU124	7679	47.5	49.2	1.7	100	4AE4	4.05	.09	8.40	6.20	115.0	2.54	1.36	21.33		14.60	22.69	.42
FAGU124	7680	49.2	51.9	2.7	100	4AD4	3.65	.09	4.30	5.60	57.0	1.78	2.06	17.41		9.90	19.47	.57
FAGU124	7681	51.9	54.5	2.6	96	4LA	2.96	.06	1.03	2.40	16.0	.48	1.90	3.19		3.43	5.09	.70
FAGU081	7682	9.1	9.7	.6	83	4A4	3.33	.06	4.00	3.50	56.0	1.10	4.77	9.50		7.50	14.27	.47
FAGU081	7683	9.7	10.0	.3	100	4L0	3.01	.03	.38	.50	7.0	.34	2.55	3.14		.88	5.69	.57
FAGU081	7684	10.0	11.0	1.0	100	4D4	3.02	.02	4.40	7.30	68.0	.82	1.81	2.08		11.70	3.89	.62
FAGU081	7685	11.0	12.7	1.7	100	4D4	3.07	.07	4.80	5.90	79.0	1.17	1.26	4.03		10.70	5.29	.55
FAGU081	7686	12.7	15.0	2.3	96	4A14	3.04	.07	3.60	3.30	52.0	1.10	.87	4.44		6.90	5.31	.48
FAGU081	7687	15.0	16.8	1.8	100	4L1	2.89	.03	.97	.58	11.0	.82	.59	2.27		1.55	2.86	.37
FAGU081	7688	16.8	18.8	2.0	100	4L1	2.95	.02	1.66	1.53	21.0	.48	1.02	1.88		3.19	2.90	.48
FAGU081	7689	18.8	20.8	2.0	95	4L1	2.96	.02	1.91	1.17	26.0	.62	1.49	2.08		3.08	3.57	.38
FAGU081	7690	20.8	22.8	2.0	100	4L1	2.93	.02	1.32	.70	19.0	.55	1.13	1.70		2.02	2.83	.35
FAGU081	7691	22.8	24.8	2.0	90	4L1	2.98	.02	1.76	.85	26.0	1.37	1.17	3.28		2.61	4.45	.33
FAGU081	7692	24.8	26.4	1.6	100	4L1	2.93	.01	2.70	2.40	34.0	.62	1.25	1.74		5.10	2.99	.47
FAGU063	7693	.0	2.5	2.5	100	4E4	4.80	.10	7.40	10.80	86.0	1.71	2.85	28.55		18.20	31.40	.59
FAGU063	7694	2.5	4.5	2.0	100	4G4	4.84	.23	5.90	8.70	135.0	2.74	.69	25.22		14.60	25.91	.60
FAGU063	7695	4.5	6.8	2.3	65	4G4	4.78	.10	5.10	10.40	105.0	1.44	.97	17.18		15.50	18.15	.67
FAGU063	7696	6.8	9.1	2.3	100	4E4	4.86	.13	7.40	11.60	101.0	1.99	1.19	27.94		19.00	29.13	.61
FAGU063	7697	9.1	9.6	.5	100	4D45	3.88	.01	10.00	4.90	139.0	1.30	1.72	13.09		14.90	14.81	.33
FAGU063	7698	9.6	11.2	1.6	100	4E4	4.38	.09	4.40	20.20	67.0	1.17	1.43	26.60		24.60	28.03	.82
FAGU063	7699	11.2	11.9	.7	57	5C3\$	3.28	.10	1.15	3.50	29.0	.96	2.99	9.79		4.65	12.78	.75
FAGU063	7700	11.9	13.3	1.4	100	5A9	2.98	.02	.19	1.95	4.0	.69	2.58	3.05		2.14	5.63	.91
FAGU064	7701	.0	1.5	1.5	87	4E4	4.91	.15	4.80	9.30	73.0	2.67	2.72	31.80		14.10	34.52	.66
FAGU064	7702	1.5	3.6	2.1	67	4E4	4.91	.23	7.50	12.30	126.0	3.09	2.12	33.76		19.80	35.88	.62
FAGU064	7703	3.6	5.6	2.0	85	4E46	4.83	.18	5.70	9.20	139.0	1.85	1.06	20.71		14.90	21.77	.62
FAGU064	7704	5.6	7.6	2.0	65	4E4	4.78	.18	5.80	10.00	138.0	2.06	1.50	19.40		15.80	20.90	.63
FAGU064	7705	7.6	9.3	1.7	71	4E4	4.67	.13	7.80	13.40	162.0	1.92	2.24	16.20		21.20	18.44	.63
FAGU064	7706	9.3	10.5	1.2	67	4E41	4.07	.02	10.10	17.60	182.0	1.44	2.36	14.20		27.70	16.56	.64
FAGU064	7707	10.5	12.1	1.6	75	4E41	4.25	.13	5.10	4.70	100.0	2.26	1.95	28.00		9.80	29.95	.48
FAGU064	7708	12.1	13.3	1.2	83	4E41	4.23	.14	4.20	4.10	66.0	2.26	1.76	26.10		8.30	27.86	.49
FAGU064	7709	13.3	16.1	2.8	50	4E4	4.50	.13	5.30	12.30	95.0	1.65	2.27	27.90		17.60	30.17	.70
FAGU064	7710	16.1	17.1	1.0	60	5A9	3.08	.03	1.13	2.70	19.0	.21	2.87	7.28		3.83	10.15	.71
FAGU064	7711	38.3	40.8	2.5	72	4E4*	4.08	.13	2.90	6.10	99.0	.01	4.81	20.50		9.00	25.31	.68
FAGA068	7712	129.8	130.5	.7	100	4A43	3.28	.05	2.90	4.70	48.0	1.03	1.10	11.00		7.60	12.10	.62
FAGA068	7713	130.5	131.0	.5	100	4A31	3.28	.02	.62	.80	16.0	.62	.85	14.40		1.42	15.25	.56
FAGA068	7714	131.0	131.7	.7	100	4L0	3.03	.02	.49	1.23	11.0	.62	.84	8.07		1.72	8.91	.72

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAO	PB+ZN	PC+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGA068	7715	131.7	132.0	.3	100	4B4	2.90	.01	2.16	3.30	36.0	.41	.77	2.24		5.46	3.01	.60
FAGA068	7716	132.0	133.0	1.0	90	4A4	3.01	.03	3.20	6.20	60.0	.75	1.09	3.38		9.40	4.47	.66
FAGA068	7717	133.0	133.5	.5	100	4L0	2.89	.01	.43	1.32	9.0	.34	1.26	3.88		1.75	5.14	.75
FAGA068	7718	133.5	135.5	2.0	50	4A0	3.16	.02	1.34	2.80	27.0	.41	.66	4.26		4.14	4.92	.68
FAGA068	7719	135.5	136.3	.8	100	4L04	2.89	.02	1.67	2.20	27.0	.55	.61	2.73		3.87	3.34	.57
FAGA068	7720	136.3	137.4	1.1	100	4B4	3.02	.02	4.60	4.10	53.0	1.44	.83	3.66		8.70	4.49	.47
FAGA068	7721	137.4	138.9	1.5	100	4B4	2.90	.02	2.90	2.30	31.0	.82	.61	2.42		5.20	3.03	.44
FAGA068	7722	138.9	140.0	1.1	100	4C0	3.05	.06	3.30	.92	34.0	1.23	.55	7.40		4.22	7.95	.22
FAGA068	7723	140.0	141.3	1.3	100	4C0	2.96	.04	1.80	2.30	31.0	.75	1.53	4.48		4.10	6.01	.56
FAGA068	7724	141.3	141.9	.6	83	4A14	3.07	.07	3.30	5.90	51.0	.96	1.25	5.92		9.20	7.17	.64
FAGA068	7725	141.9	142.3	.4	100	5D4*	2.99	.03	.33	1.70	10.0	.48	4.08	4.35		2.03	8.43	.84
FAGA068	7726	142.3	143.0	.7	71	4A1	3.18	.11	.39	.56	15.0	1.10	.89	14.10		.95	14.99	.59
FAGA068	7727	143.0	143.5	.5	100	4D0	3.24	.16	2.30	3.50	43.0	1.30	1.06	13.20		5.80	14.26	.60
FAGA068	7728	143.5	144.0	.5	80	5C4@	2.94	.02	.50	.71	8.0	.41	5.55	2.30		1.21	7.85	.59
FAGA068	7729	144.0	145.0	1.0	100	4D0	3.33	.05	.42	7.60	62.0	.89	1.81	10.40		8.02	12.21	.95
FAGA068	7730	145.0	145.6	.6	83	4E14	3.62	.02	7.00	14.80	96.0	1.17	3.88	11.00		21.80	14.88	.68
FAGA068	7731	145.6	146.9	1.3	100	4A41	3.28	.04	3.40	7.70	57.0	1.03	1.76	9.96		11.10	11.72	.69
FAGA068	7732	146.9	147.4	.5	80	4D4	3.13	.02	1.98	3.60	33.0	.75	2.49	7.29		5.58	9.78	.65
FAGA068	7733	157.0	158.1	1.1	91	4L14	3.52	.17	1.96	3.90	39.0	1.92	1.64	17.10		5.86	18.74	.67
FAGA068	7734	158.1	158.5	.4	100	4A34	3.02	.05	1.58	3.70	26.0	.75	1.70	6.19		5.28	7.89	.70
FAGA068	7735	163.4	165.5	2.1	100	4A1	2.95	.06	1.23	2.09	21.0	.82	1.23	4.73		3.32	5.96	.63
FAGA068	7736	165.5	167.0	1.5	100	4A14	2.91	.06	1.96	3.80	32.0	.89	.97	3.09		5.76	4.06	.66
FAGA068	7737	167.0	168.9	1.9	95	4A1	2.90	.04	1.45	2.40	25.0	.75	.82	5.29		3.85	6.11	.62
FAGA068	7738	168.9	170.7	1.8	100	4A1	2.89	.04	1.48	3.00	21.0	1.03	.76	3.03		4.48	3.79	.67
FAGA068	7739	170.7	173.1	2.4	100	4A13	3.30	.03	2.80	5.40	43.0	1.03	1.30	11.90		8.20	13.20	.66
FAGA068	7740	173.1	175.9	2.8	96	4A13	3.41	.06	3.00	5.40	53.0	1.03	1.58	15.00		8.40	16.58	.64
FAGA068	7741	175.9	177.9	2.0	100	4A14	2.93	.04	1.43	4.00	25.0	.82	1.27	4.30		5.43	5.57	.74
FAGA068	7742	177.9	179.7	1.8	100	4A14	2.94	.05	2.19	3.90	31.0	.89	.90	3.06		6.09	3.96	.64
FAGA068	7743	179.7	181.6	1.9	100	4A14	2.92	.03	1.25	4.10	21.0	.82	1.05	2.90		5.35	3.95	.77
FAGA068	7744	181.6	183.3	1.7	100	4A14	2.96	.02	1.77	3.60	40.0	.62	.86	2.88		5.37	3.74	.67
FAGA068	7745	183.3	185.3	2.0	100	4A14	3.11	.03	1.91	5.30	42.0	.82	1.26	3.76		7.21	5.02	.74
FAGA068	7746	185.3	187.3	2.0	90	4A14	3.41	.06	5.00	6.40	74.0	1.23	1.90	10.80		11.40	12.70	.56
FAGA068	7747	187.3	188.7	1.4	100	4D0	3.36	.10	4.00	2.16	53.0	1.51	1.08	16.34		6.16	17.42	.35
FAGA068	7748	190.2	191.4	1.2	100	4D45	3.59	.02	6.30	13.50	95.0	1.17	2.13	11.40		19.80	13.53	.68
FAGA068	7749	191.4	192.9	1.5	80	4D45	3.52	.02	4.60	10.60	75.0	1.37	1.88	12.30		15.20	14.18	.70
FAGA068	7750	192.9	193.4	.5	100	4A1	3.45	.03	1.00	3.50	22.0	.89	2.37	16.40		4.50	18.77	.78
FAGA068	7751	199.9	201.7	1.8	83	4D4	3.38	.06	5.20	5.50	71.0	1.03	2.80	8.65		10.70	11.45	.51
FAGA068	7752	201.7	203.5	1.8	100	4A13		.18	.47	1.07	14.0					1.54		.70
FAGA068	7753	208.0	209.7	1.7	100	4A0	3.18	.12	1.93	2.17	30.0	1.78	2.80	7.64		4.10	10.44	.53
FAGA068	7754	209.7	210.6	.9	89	4L0	2.96	.01	.04	.07	5.0	.21	3.28	2.01		.11	5.29	.64
FAGA068	7755	210.6	212.3	1.7	100	4A14	3.31	.11	2.70	2.90	39.0	1.65	1.62	12.20		5.60	13.82	.52
FAGA068	7756	212.3	213.7	1.4	93	4A1	3.65	.22	1.51	3.30	42.0	2.54	1.65	20.70		4.81	22.35	.69
FAGA068	7757	213.7	215.3	1.6	88	4A1	3.40	.14	1.23	3.40	31.0	1.78	1.75	15.10		4.63	16.85	.73
FAGA068	7758	222.5	223.5	1.0	100	4K4	3.30	.08	3.30	6.80	66.0	.48	6.50	7.76		10.10	14.26	.67
FAGA068	7759	223.5	224.0	.5	80	4D4	3.56	.03	5.00	8.50	90.0	1.51	2.17	11.60		13.50	13.77	.63
FAGA068	7760	224.0	225.5	1.5	100	4A14	3.44	.12	4.20	5.00	62.0	1.85	2.18	12.50		9.20	14.68	.54
FAGA068	7761	244.0	245.7	1.7	100	4A13	3.19	.08	1.98	2.60	26.0	.89	1.32	9.93		4.58	11.25	.57
FAGA068	7762	245.7	247.5	1.8	94	4A13	3.24	.09	1.12	1.55	25.0	.75	1.56	12.60		2.67	14.16	.58
FAGA068	7763	249.5	250.5	1.0	90	4A13		.08	.93	1.39	17.0					2.32		.60
FAGA068	7764	297.6	298.1	.5	80	4H0		.24	.30	.78	32.0					1.08		.72

DDH	SAMPLE	----DEPTHS----		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAO	PB+ZN	PO+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGA068	7765	298.1	299.0	.9	100	4L0		.01	.04	.11	5.0					.15		.73
FAGA068	7766	299.0	299.9	.9	89	4C0		.24	.55	.61	21.0					1.16		.53
FAGA068	7767	299.9	300.5	.6	100	4E48	3.18	.30	4.10	5.40	50.0	.62	6.20	21.70		9.50	27.90	.57
FAGA068	7768	300.5	301.0	.5	80	4C0	3.26	.10	1.11	1.92	19.0	.41	6.27	8.33		3.03	14.60	.63
FAGA068	7769	301.0	301.3	.3	100	4E18	3.69	.22	4.70	4.20	48.0	.41	11.70	10.30		8.90	22.00	.47
FAGA068	7770	301.3	303.1	1.8	100	4L0	3.04	.05	.34	.42	7.0	.55	5.11	3.19		.76	8.30	.55
FAGA068	7771	303.1	304.8	1.7	71	4E1*	3.74	.15	2.70	2.50	26.0	.34	11.94	15.20		5.20	27.14	.48
FAGA068	7772	330.4	332.2	1.8	89	4G4	3.97	.10	5.50	7.40	85.0	1.10	3.34	10.62		12.90	13.96	.57
FAGA068	7773	332.2	334.0	1.8	94	4G0	3.80	.13	3.90	5.70	69.0	1.44	3.02	10.30		9.60	13.32	.59
FAGA068	7774	334.0	334.6	.6	100	4G4	4.18	.18	5.00	7.10	94.0	1.71	1.71	11.80		12.10	13.51	.59
FAGA068	7775	334.6	335.7	1.1	100	4E0	4.28	.22	2.20	2.60	34.0	1.37	5.77	27.70		4.80	33.47	.54
FAGA053	7776	140.5	141.7	1.2	100	4E14	3.77	.09	6.00	11.40	99.0	1.10	2.08	14.70		17.40	16.78	.66
FAGA053	7777	141.7	145.1	3.4	9	4A4	3.72	.06	6.60	15.00	126.0	1.10	.92	16.50		21.60	17.42	.69
FAGA053	7778	145.1	145.7	.6	33	4E14	4.46	.26	3.50	6.90	60.0	1.92	1.45	32.00		10.40	33.45	.66
FAGA053	7779	145.7	147.2	1.5	87	4E4	4.69	.09	3.60	8.20	68.0	1.03	1.25	34.00		11.80	35.25	.69
FAGA053	7780	147.2	148.0	.8	50	4E4	4.58	.05	2.40	7.30	45.0	.89	1.46	35.30		9.70	36.76	.75
FAGA053	7781	148.0	150.6	2.6	46	4E4#	4.45	.18	7.90	17.80	146.0	1.44	.99	23.40		25.70	24.39	.69
FAGA053	7782	150.6	151.8	1.2	42	4L04	3.02	.02	1.56	4.10	24.0	.41	1.56	4.94		5.66	6.50	.72
FAGA053	7783	151.8	155.9	4.1	49	4L14	2.93	.02	2.03	3.30	28.0	.48	.70	3.37		5.33	4.07	.62
FAGA053	7784	155.9	157.4	1.5	80	4A14	3.08	.05	3.20	4.80	42.0	.62	.92	5.19		8.00	6.11	.60
FAGA053	7785	157.4	159.0	1.6	81	4A1	3.14	.09	1.84	1.56	27.0	1.10	.93	9.25		3.40	10.18	.46
FAGA053	7786	159.0	161.4	2.4	88	4L14	2.92	.02	1.30	3.30	26.0	.41	1.16	2.54		4.60	3.70	.72
FAGA053	7787	171.5	173.0	1.5	100	4L21		.08	.60	1.83	17.0					2.43		.75
FAGA053	7788	234.6	236.4	1.8	61	4A4	2.96	.10	.45	.91	15.0	2.61	.85	10.46		1.36	11.31	.67
FAGA053	7789	236.4	238.4	2.0	75	4A4	3.12	.06	2.70	5.70	46.0	.55	1.28	5.60		8.40	6.88	.68
FAGA053	7790	238.4	240.1	1.7	100	4A1	3.39	.09	.46	.59	17.0	.62	1.17	19.00		1.05	20.17	.56
FAGA053	7791	240.1	242.8	2.7	78	4E4	4.60	.16	4.00	5.80	72.0	1.44	1.68	32.50		9.80	34.18	.59
FAGA053	7792	242.8	245.5	2.7	81	4E4	4.35	.10	4.20	7.40	78.0	.75	1.75	23.30		11.60	25.05	.64
FAGA053	7793	245.5	247.8	2.3	91	4E0	4.80	.14	2.80	2.00	37.0	1.58	1.11	36.40		4.80	37.51	.42
FAGA053	7794	247.8	249.9	2.1	90	4E0	4.83	.26	1.62	1.51	33.0	1.23	1.09	39.50		3.13	40.59	.48
FAGA053	7795	249.9	252.4	2.5	76	4E4	4.64	.21	2.18	3.20	53.0	1.78	1.41	37.30		5.38	38.71	.59
FAGA053	7796	252.4	254.5	2.1	86	4E4	4.64	.15	5.60	10.70	115.0	1.37	1.41	37.30		16.30	38.71	.66
FAGA053	7797	254.5	256.3	1.8	100	4E4	4.70	.13	4.20	7.40	66.0	1.17	2.64	33.30		11.60	35.94	.64
FAGA053	7798	256.3	257.3	1.0	90	4G4#	4.53	.13	4.40	7.10	72.0	1.37	1.17	28.58		11.50	29.75	.62
FAGA053	7799	257.3	258.9	1.6	100	4G4#	4.61	.13	4.60	7.60	85.0	1.37	.80	26.60		12.20	27.40	.62
FAGA053	7800	258.9	259.4	.5	100	4A4	3.50	.03	7.10	12.40	108.0	1.10	1.23	10.30		19.50	11.53	.64
FAGU063	7801	13.3	14.7	1.4	100	5A9		.01	.08	.78	1.0					.86		.91
FAGU063	7802	39.6	41.1	1.5	87	4E47	4.40	.27	6.00	4.20	58.0	.14	16.42	20.70		10.20	37.12	.41
FAGU063	7803	41.1	42.6	1.5	100	4E47	4.30	.33	5.90	3.90	60.0	.14	14.97	21.70		9.80	36.67	.40
FAGU063	7804	56.7	58.0	1.3	100	4G4#	4.39	.08	5.30	5.80	83.0	.55	3.04	13.60		11.10	16.64	.52
FAGU063	7805	58.0	59.4	1.4	100	4G0#	4.01	.25	2.70	2.80	41.0	.89	7.12	22.80		5.50	29.92	.51
FAGU063	7806	59.4	59.8	.4	100	4L0	3.20	.08	.69	1.17	14.0	.34	3.07	8.90		1.86	11.97	.63
FAGU063	7807	59.8	60.9	1.1	100	4G48	4.42	.16	5.50	8.40	95.0	.48	3.18	10.00		13.90	13.18	.60
FAGU063	7808	60.9	62.7	1.8	94	4G48	4.57	.05	7.00	8.40	117.0	.34	1.51	6.40		15.40	7.91	.55
FAGU063	7809	62.7	64.4	1.7	88	4KEG	3.95	.03	12.90	12.10	211.0	.34	4.23	10.85		25.00	15.08	.48
FAGU043	7810	.0	3.0	3.0	67	4CL	4.38	.04	9.90	17.60	177.0	1.03	1.80	18.50		27.50	20.30	.64
FAGU043	7811	3.0	5.0	2.0	95	4CL	2.93	.05	1.37	1.10	16.0	.34	2.53	4.77		2.47	7.30	.45
FAGU043	7812	6.8	7.6	.8	100	4CL	2.89	.06	1.53	2.24	21.0	.41	1.12	3.55		3.77	4.67	.59
FAGU043	7813	7.6	9.1	1.5	100	4A4	2.97	.04	4.05	4.35	50.0	.89	1.59	3.52		8.40	5.11	.52
FAGU043	7814	9.1	10.7	1.6	100	4A4	2.86	.05	4.50	4.70	58.0	1.17	1.07	4.54		9.20	5.61	.51

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAO	PB+ZN	PC+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGU043	7815	10.7	12.7	2.0	100	4A4	3.53	.01	4.32	9.10	77.0	1.03	1.23	14.60		13.42	15.83	.68
FAGU043	7816	12.7	14.4	1.7	100	4E14	2.89	.04	11.21	19.60	183.0	.34	1.45	3.75		30.81	5.20	.64
FAGU043	7817	14.4	16.0	1.6	100	4E14	4.64	.01	10.40	19.10	174.0	1.30	1.81	20.20		29.50	22.01	.65
FAGU043	7818	16.0	17.7	1.7	100	4E14	3.87	.01	9.50	17.40	178.0	1.44	1.79	11.50		26.90	13.29	.65
FAGU043	7819	17.7	19.2	1.5	100	4E4	4.66	.10	12.60	32.40	202.0	1.85	1.45	16.00		45.00	17.45	.72
FAGU043	7820	19.2	20.7	1.5	100	4E14	3.86	.01	8.40	14.60	144.0	1.44	1.44	12.80		23.00	14.24	.63
FAGU043	7821	20.7	21.8	1.1	100	4A34	3.46	.01	6.80	13.10	109.0	1.30	1.48	8.70		19.90	10.18	.66
FAGU043	7822	21.8	23.3	1.5	93	4E4	4.58	.08	7.50	14.20	136.0	1.51	.90	27.70		21.70	28.60	.65
FAGU043	7823	23.3	24.7	1.4	100	4E4	4.45	.07	7.50	14.90	128.0	1.78	1.21	24.30		22.40	25.51	.67
FAGU047	7824	.0	2.4	2.4	100	4D4	3.72	.20	7.30	8.70	119.0	1.30	2.26	15.00		16.00	17.26	.54
FAGU047	7825	2.4	4.2	1.8	100	4A4	3.63	.07	6.10	4.60	80.0	2.19	1.07	16.70		10.70	17.77	.43
FAGU047	7826	4.2	5.0	.8	100	4C3	3.64	.12	2.80	1.71	31.0	1.30	2.29	21.20		4.51	23.49	.38
FAGU047	7827	5.0	5.8	.8	87	5D4*	3.87	.07	3.50	3.10	47.0	1.03	2.81	22.40		6.60	25.21	.47
FAGU047	7828	5.8	6.4	.6	100	4C0	2.96	.05	.21	.04	2.0	.41	3.68	2.71		.25	6.39	.16
FAGU047	7829	6.4	8.2	1.8	100	5D4*	3.01	.03	.64	.90	9.0	.48	4.23	5.00		1.54	9.23	.58
FAGU047	7830	8.2	10.7	2.5	100	4A14	3.73	.08	3.70	2.25	42.0	1.51	1.08	21.70		5.95	22.78	.38
FAGU047	7831	10.7	12.8	2.1	100	4A14	3.64	.08	3.60	6.10	62.0	1.51	1.40	17.60		9.70	19.00	.63
FAGU047	7832	12.8	15.0	2.2	100	4A14	3.23	.02	3.00	4.70	53.0	1.23	2.12	10.90		7.70	13.02	.61
FAGU047	7833	15.0	16.3	1.3	100	4D4	3.51	.03	7.40	13.50	132.0	.82	2.80	12.70		20.90	15.50	.65
FAGU047	7834	16.3	17.8	1.5	100	4D4	3.80	.08	5.40	8.60	94.0	1.99	1.63	17.90		14.00	19.53	.61
FAGU047	7835	17.8	19.7	1.9	100	4G4#	4.42	.12	8.00	24.00	176.0	1.99	2.64	18.00		32.00	20.64	.75
FAGU047	7836	19.7	21.0	1.3	100	4D4	3.72	.02	7.50	16.90	107.0	.96	2.60	10.60		24.40	13.20	.69
FAGU047	7837	21.0	22.2	1.2	92	4G4#	4.42	.08	11.60	26.90	207.0	1.99	1.34	14.70		38.50	16.04	.70
FAGU047	7838	30.3	32.2	1.9	100	4AE4	3.65	.11	5.10	9.20	94.0	1.78	1.80	14.50		14.30	16.30	.64
FAGU047	7839	32.2	33.7	1.5	100	4K47	3.65	.08	4.10	9.00	81.0	.41	5.92	7.80		13.10	13.72	.69
FAGU047	7840	33.7	34.4	.7	71	4D45	3.60	.05	4.70	8.60	83.0	2.13	1.94	12.80		13.30	14.74	.65
FAGU047	7841	37.5	39.5	2.0	90	4A0	3.74	.10	3.90	5.00	62.0	1.92	1.03	20.60		8.90	21.63	.56
FAGU047	7842	57.5	59.4	1.9	100	4EG4	4.47	.14	5.20	8.30	88.0	1.85	1.17	29.10		13.50	30.27	.61
FAGU047	7843	59.4	61.2	1.8	100	4EG4	3.99	.14	3.90	4.60	78.0	3.09	1.03	29.10		8.50	30.13	.54
FAGU047	7844	61.2	62.9	1.7	100	4EG4	4.70	.20	5.40	8.30	92.0	2.26	.59	31.90		13.70	32.49	.61
FAGU047	7845	62.9	64.8	1.9	100	4EG4	4.50	.16	5.60	10.70	97.0	1.85	.78	28.60		16.30	29.38	.66
FAGU047	7846	64.8	65.4	.6	100	4A0	3.30	.09	1.56	2.60	24.0	.82	.70	13.10		4.16	13.80	.63
FAGU150	7847	.0	2.1	2.1	57	4A4	3.23	.06	5.50	8.17	73.0	1.37	1.16	6.70		13.67	7.86	.60
FAGU150	7848	2.1	4.1	2.0	100	4A4	2.99	.04	2.40	3.66	36.0	.82	.81	5.00		6.06	5.81	.60
FAGU150	7849	4.1	6.1	2.0	100	4A0	3.17	.05	1.57	.69	24.0	1.30	.62	11.00		2.26	11.62	.31
FAGU150	7850	6.1	7.8	1.7	100	4A0		.06	1.41	.38	30.0					1.79		.21
FAGA053	7851	259.4	261.7	2.3	100	4A1	3.25	.09	.62	1.09	21.0	.69	.97	14.10		1.71	15.07	.64
FAGA053	7852	261.7	263.6	1.9	100	4A1	3.17	.07	1.03	2.29	22.0	.62	1.57	10.20		3.32	11.77	.69
FAGA053	7853	263.6	264.2	.6	83	4E4	4.72	.12	3.80	7.20	51.0	1.17	1.94	34.10		11.00	36.04	.65
FAGA053	7854	264.2	265.8	1.6	94	4A13	3.41	.10	2.80	5.30	51.0	1.30	1.52	14.80		8.10	16.32	.65
FAGA053	7855	265.8	266.9	1.1	100	4A13	3.46	.12	2.80	4.50	54.0	.96	1.05	16.30		7.30	17.35	.62
FAGA053	7856	266.9	267.5	.6	83	4G4#	4.42	.31	7.40	17.10	132.0	2.40	1.22	22.60		24.50	23.82	.70
FAGA053	7857	267.5	269.9	2.4	100	4A4	3.56	.13	3.70	7.20	56.0	1.17	1.15	16.90		10.90	18.05	.66
FAGA053	7858	269.9	272.3	2.4	100	4A4	3.29	.10	4.60	6.70	69.0	1.37	1.26	12.49		11.30	13.75	.59
FAGA053	7859	272.3	273.7	1.4	100	4A13		.24	.44	.49	22.0					.93		.53
FAGA053	7860	273.7	277.2	3.5	43	4A13		.30	.14	.49	17.0					.63		.78
FAGA053	7861	277.2	279.0	1.8	100	4A13		.28	.18	1.20	24.0					1.38		.87
FAGA053	7862	279.0	281.2	2.2	100	4A13		.39	.09	.64	38.0					.73		.88
FAGA053	7863	281.2	283.8	2.6	100	4C0		.34	.72	1.14	49.0					1.86		.61
FAGA053	7864	331.3	333.2	1.9	100	4E#4	4.11	.22	4.00	4.30	54.0	.55	7.94	23.70		8.30	31.64	.52

DDH	SAMPLE	----DEPTHS----		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAO	PB+ZN	PC+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGA053	7865	333.2	335.1	1.9	100	4E#4	4.12	.21	3.90	3.70	43.0	.69	7.45	23.60		7.60	31.05	.49
FAGA053	7866	343.5	345.3	1.8	17	4D*4			4.73	6.72	61.4					11.45		.59
FAGA053	7867	345.3	347.8	2.5	36	4LG			.04	.03	1.0					.07		.42
FAGA053	7868	347.8	349.0	1.2	50	4E15			.07	.05	1.7					.12		.42
FAGU147	7869	.0	6.1	6.1	20	4A0		.06	.48	1.54	14.0					2.02		.76
FAGU147	7870	6.1	9.1	3.0	77	4A0		.21	.31	.81	18.0					1.12		.72
FAGU147	7871	9.1	11.2	2.1	100	4A0		.25	.33	1.19	19.0					1.52		.78
FAGU147	7872	11.2	13.2	2.0	100	4A0		.16	.27	1.04	15.0					1.31		.79
FAGU147	7873	13.2	15.2	2.0	95	4A0		.27	.29	.95	19.0					1.24		.77
FAGU147	7874	15.2	17.2	2.0	100	4A0	3.17	.13	.26	.86	13.0	.69	1.24	11.70		1.12	12.94	.77
FAGU147	7875	17.2	18.7	1.5	100	4A0	3.32	.17	.21	.69	17.0	.69	1.14	17.90		.90	19.04	.77
FAGU147	7876	18.7	20.2	1.5	100	4A4	3.40	.13	3.40	4.60	63.0	2.33	1.37	14.40		8.00	15.77	.58
FAGU147	7877	20.2	21.6	1.4	100	4E4	4.51	.21	6.50	15.80	102.0	2.88	3.05	23.20		22.30	26.25	.71
FAGU147	7878	21.6	22.5	.9	78	4D4	3.37	.24	7.50	14.40	122.0	2.95	1.52	10.80		21.90	12.32	.66
FAGU147	7879	22.5	24.8	2.3	100	4GE4	4.73	.19	5.30	10.40	93.0	2.54	1.68	27.40		15.70	29.08	.66
FAGU147	7880	24.8	26.5	1.7	76	4D4	3.45	.14	4.60	11.90	103.0	1.85	1.33	8.70		16.50	10.03	.72
FAGU147	7881	26.5	27.8	1.3	100	4EG	4.76	.27	3.30	6.10	82.0	2.33	2.86	30.30		9.40	33.16	.65
FAGU147	7882	27.8	29.0	1.2	50	4G4	4.73	.12	4.70	9.70	88.0	1.78	.95	19.30		14.40	20.25	.67
FAGU147	7883	29.0	31.0	2.0	100	4E4	4.63	.13	5.70	10.70	89.0	4.52	2.05	12.70		16.40	14.75	.65
FAGU147	7884	31.0	31.8	.8	50	5D4*	3.10	.02	.17	3.50	5.0	1.65	8.06	3.31		3.67	11.37	.95
FAGU147	7885	31.8	33.3	1.5	47	4E4	4.70	.26	3.90	8.20	91.0	1.37	3.79	33.50		12.10	37.29	.68
FAGU147	7886	33.3	33.7	.4	100	5D4*	3.96	.07	3.60	8.10	63.0	1.30	5.82	10.70		11.70	16.52	.69
FAGU147	7887	33.7	34.6	.9	56	4G4	4.80	.11	4.90	10.10	87.0	1.44	3.01	29.70		15.00	32.71	.67
FAGU147	7888	34.6	36.4	1.8	94	4A4	3.33	.30	1.99	3.70	27.0	1.37	2.10	17.20		5.69	19.30	.65
FAGU147	7889	51.2	53.3	2.1	90	4A0		.39	.51	1.28	36.0					1.79		.72
FAGU147	7890	53.3	56.0	2.7	100	4A0		.40	.12	.57	13.0					.69		.83
FAGU147	7891	56.0	56.6	.6	100	4E0		.48	.16	.65	15.0					.81		.80
FAGU147	7892	56.6	57.4	.8	75	4A0		.34	.36	.51	13.0					.87		.59
FAGU126	7893	.0	3.7	3.7	38	4A1	2.89	.04	1.37	1.74	25.0	.55	1.10	3.61		3.11	4.71	.56
FAGU126	7894	3.7	6.1	2.4	67	4A14	2.95	.06	1.62	4.20	30.0	.55	.92	3.40		5.82	4.32	.72
FAGU126	7895	6.1	7.6	1.5	100	4D0	3.15	.11	2.70	3.00	47.0	1.17	.96	8.60		5.70	9.56	.53
FAGU126	7896	7.6	9.7	2.1	76	4C0	2.88	.07	1.53	2.70	28.0	6.17	.84	3.67		4.23	4.51	.64
FAGU126	7897	9.7	12.2	2.5	100	4A14	2.98	.09	1.62	4.20	36.0	.89	1.21	3.59		5.82	4.80	.72
FAGU126	7898	12.2	15.2	3.0	97	4A14	2.97	.07	2.90	5.80	44.0	.62	1.07	2.07		8.70	3.14	.67
FAGU126	7899	15.2	17.4	2.2	91	4A14	2.93	.06	1.70	4.90	34.0	3.02	1.00	1.17		6.60	2.17	.74
FAGU126	7900	17.4	19.4	2.0	100	4A14	2.80	.02	1.81	4.70	33.0	.34	.88	.75		6.51	1.63	.72
FAGU048	7901	12.5	12.9	.4	100	5D4*	3.29	.07	.07	.38	9.0	.34	5.79	7.20		.45	12.99	.84
FAGU048	7902	12.9	14.7	1.8	100	4E1	3.54	.06	2.60	5.10	44.0	.89	1.71	17.30		7.70	19.01	.66
FAGU048	7903	22.3	24.4	2.1	81	4D5	3.06	.04	2.60	6.20	56.0	.55	1.34	7.90		8.80	9.24	.70
FAGU048	7904	24.4	25.9	1.5	100	4D5	4.22	.06	5.10	12.00	115.0	.89	1.64	9.80		17.10	11.44	.70
FAGU048	7905	25.9	27.2	1.3	100	4D5	3.40	.09	3.70	7.80	69.0	.82	1.80	9.20		11.50	11.00	.68
FAGU048	7906	28.8	31.1	2.3	100	4L14	3.08	.04	2.30	6.50	33.0	.62	1.57	5.10		8.80	6.67	.74
FAGU048	7907	32.1	33.2	1.1	91	4LD	2.89	.01	1.34	3.80	26.0	.48	.85	4.03		5.14	4.88	.74
FAGU048	7908	33.2	35.3	2.1	81	4LD	3.27	.02	4.30	8.20	72.0	1.10	1.12	10.40		12.50	11.52	.66
FAGU048	7909	35.3	37.4	2.1	95	4LD	3.32	.06	3.10	7.30	60.0	1.17	2.03	8.00		10.40	10.03	.70
FAGU048	7910	37.4	38.0	.6	100	5D4*	3.03	.03	.37	2.40	13.0	.27	5.34	2.36		2.77	7.70	.87
FAGU048	7911	38.0	39.6	1.6	100	4D453	3.24	.03	4.80	10.10	77.0	1.17	1.80	13.60		14.90	15.40	.68
FAGU048	7912	39.6	41.6	2.0	100	4D453	3.72	.06	9.10	13.10	152.0	1.44	2.46	15.50		22.20	17.96	.59
FAGU048	7913	41.6	43.6	2.0	100	4D453	3.40	.11	5.30	13.10	83.0	1.51	3.12	10.90		18.40	14.02	.71
FAGU048	7914	43.6	45.5	1.9	100	4D453	3.40	.12	4.40	7.20	73.0	2.06	1.66	15.40		11.60	17.06	.62

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAO	PB+ZN	PC+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGU048	7915	45.5	48.0	2.5	100	4A1	2.90	.07	.71	1.21	18.0	.62	1.37	5.30		1.92	6.67	.63
FAGU048	7916	61.7	62.7	1.0	100	4A0	3.08	.03	.51	1.83	8.0	.34	4.20	8.80		2.34	13.00	.78
FAGU048	7917	62.7	64.5	1.8	94	4A1	3.09	.03	.50	2.10	11.0	.34	1.60	11.00		2.60	12.60	.81
FAGU048	7918	64.5	66.2	1.7	100	4A1	3.14	.09	1.25	2.80	18.0	1.03	1.85	11.00		4.05	12.85	.69
FAGU048	7919	66.2	67.1	.9	100	4H1	3.68	.15	.89	1.47	24.0	1.30	8.71	22.80		2.36	31.51	.62
FAGU048	7920	67.1	68.2	1.1	100	4H4	4.31	.24	7.20	14.80	157.0	1.03	8.98	18.00		22.00	26.98	.67
FAGU048	7921	68.2	70.1	1.9	100	4H1	3.80	.28	3.10	5.50	70.0	.89	17.81	16.20		8.60	34.01	.64
FAGU048	7922	70.1	70.6	.5	100	4E46	4.20	.20	4.70	9.00	104.0	1.85	2.19	28.00		13.70	30.19	.66
FAGU048	7923	70.6	71.8	1.2	92	4A1	3.29	.16	6.40	8.70	120.0	.55	5.75	8.70		15.10	14.45	.58
FAGU048	7924	71.8	72.8	1.0	70	4LH	3.50	.13	4.90	9.60	86.0	.69	3.63	13.40		14.50	17.03	.66
FAGU048	7925	72.8	73.2	.4	100	1000	2.98	.04	.13	.20	6.0	.48	.93	3.80		.33	4.73	.61
FAGU048	7926	73.2	73.6	.4	100	4J41	3.66	.06	10.20	18.90	180.0	2.33	4.61	11.80		29.10	16.41	.65
FAGU048	7927	73.6	75.5	1.9	100	4E46	4.11	.26	4.10	8.20	66.0	1.58	1.19	28.60		12.30	29.79	.67
FAGU048	7928	75.5	77.3	1.8	100	4E46	4.19	.22	5.70	11.50	124.0	1.58	.90	27.50		17.20	28.40	.67
FAGU048	7929	77.3	79.2	1.9	100	4A1	3.35	.10	2.20	2.30	36.0	1.10	.99	14.60		4.50	15.59	.51
FAGU048	7930	79.2	80.6	1.4	100	4A1	3.06	.10	.13	.06	11.0	.62	.84	15.90		.19	16.74	.32
FAGU048	7931	80.6	81.8	1.2	100	4A1	3.05	.06	.65	1.13	13.0	.69	.69	13.80		1.78	14.49	.63
FAGU048	7932	100.1	101.4	1.3	100	4C0		.09	.69	.84	13.0					1.53		.55
FAGU048	7933	101.4	103.1	1.7	100	4A1		.09	.32	.58	9.0					.90		.64
FAGU048	7934	103.1	104.7	1.6	100	4A1		.13	.15	.55	8.0					.70		.79
FAGA105	7935	99.4	100.0	.6	83	4E86a	4.37	.32	2.90	1.66	40.0	1.37	6.48	30.70		4.56	37.18	.36
FAGA105	7936	100.0	101.9	1.9	100	4E86#	3.89	.18	2.60	2.30	33.0	.69	7.78	20.10		4.90	27.88	.47
FAGA105	7937	101.9	102.8	.9	78	4E8*	3.96	.13	2.20	1.04	28.0	.62	6.26	25.93		3.24	32.19	.32
FAGA105	7938	102.8	104.8	2.0	100	4A19	3.51	.24	.82	1.38	19.0	1.17	3.71	19.40		2.20	23.11	.63
FAGA105	7939	104.8	106.8	2.0	100	4A19	3.29	.20	.15	.17	8.0	1.17	2.18	15.50		.32	17.68	.53
FAGA105	7940	106.8	109.3	2.5	100	4A19		.21	.19	.20	10.0					.39		.51
FAGA105	7941	111.1	112.4	1.3	69	4C0		.32	.14	.36	11.0					.50		.72
FAGA105	7942	112.9	113.6	.7	86	4G4#	3.99	.14	7.80	9.20	106.0	1.51	2.90	15.90		17.00	18.80	.54
FAGA105	7943	113.6	114.2	.6	100	4D0	3.37	.08	6.30	4.80	81.0	1.71	3.04	9.30		11.10	12.34	.43
FAGA105	7944	114.2	116.5	2.3	100	4CE*		.27	.31	.66	11.0					.97		.68
FAGA105	7945	116.5	118.5	2.0	90	4A1		.19	.19	.27	10.0					.46		.59
FAGA105	7946	118.5	120.4	1.9	100	4A1		.17	.30	.35	13.0					.65		.54
FAGA105	7947	120.4	122.7	2.3	100	4C0		.21	.09	.43	7.0					.52		.83
FAGA105	7948	122.7	124.3	1.6	75	4D0	3.41	.12	2.50	3.60	30.0	.82	4.69	12.30		6.10	16.99	.59
FAGA105	7949	124.3	125.6	1.3	100	4C0	3.54	.28	.27	.55	17.0	.01	4.39	20.00		.82	24.39	.67
FAGA105	7950	125.6	126.9	1.3	100	4C0	3.54	.21	.78	1.86	17.0	.62	4.46	17.80		2.64	22.26	.70
FAGA069	7951	213.2	215.8	2.6	81	4K4	3.27	.03	2.90	5.00	52.0	.62	3.25	6.80		7.90	10.05	.63
FAGA069	7952	215.8	217.8	2.0	100	4K0	3.38	.02	.69	2.20	20.0	.48	1.34	15.00		2.89	16.34	.76
FAGA069	7953	217.8	219.9	2.1	100	4K4	3.36	.02	2.60	6.60	35.0	.55	3.28	8.90		9.20	12.18	.72
FAGA069	7954	222.1	222.5	.4	100	4A0	3.02	.02	1.32	2.70	21.0	1.30	2.28	3.80		4.02	6.08	.67
FAGA069	7955	232.2	234.1	1.9	100	4A14	3.50	.11	3.10	4.90	51.0	2.13	1.31	16.40		8.00	17.71	.61
FAGA069	7956	237.7	239.4	1.7	94	4A14	3.09	.15	3.70	5.20	64.0	1.51	1.30	10.00		8.90	11.30	.58
FAGA069	7957	239.4	240.4	1.0	100	5B69	2.90	.01	.42	1.75	8.0	.48	2.42	.80		2.17	3.22	.81
FAGA069	7958	241.8	243.4	1.6	100	4A10	3.00	.08	1.40	2.50	23.0	1.03	1.13	4.83		3.90	5.96	.64
FAGA069	7959	304.6	305.1	.5	100	4A10	3.10	.07	.66	1.11	17.0	1.23	.85	10.20		1.77	11.05	.63
FAGA069	7960	305.1	306.8	1.7	94	4G4#	4.45	.15	5.10	10.40	91.0	2.06	1.04	21.40		15.50	22.44	.67
FAGA069	7961	306.8	307.8	1.0	90	4E4	4.45	.31	3.10	3.70	56.0	2.67	1.30	32.40		6.80	33.70	.54
FAGA069	7962	307.8	308.5	.7	71	4G4#	4.60	.18	5.40	7.50	95.0	2.26	.75	29.10		12.90	29.85	.58
FAGA069	7963	308.5	309.4	.9	100	4E4	4.45	.18	4.00	3.40	57.0	1.99	1.23	31.80		7.40	33.03	.46
FAGA069	7964	309.4	309.8	.4	100	4G4#	4.57	.25	7.70	8.40	117.0	3.09	.93	28.30		16.10	29.23	.52

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAO	PB+ZN	PO+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGA069	7965	309.8	310.7	.9	100	4E4#	4.58	.26	4.90	5.90	78.0	2.54	.95	33.20		10.80	34.15	.55
FAGA069	7966	310.7	312.4	1.7	100	4E4#	4.23	.17	3.60	4.10	72.0	1.58	.78	32.90		7.70	33.68	.53
FAGA069	7967	315.5	317.3	1.8	94	4A14	3.18	.07	2.60	3.50	40.0	1.30	1.02	13.30		6.10	14.32	.57
FAGA069	7968	317.3	320.3	3.0	100	4A14	3.22	.06	2.70	3.40	41.0	1.44	.94	8.60		6.10	9.54	.56
FAGA069	7969	320.3	323.1	2.8	100	4A10	3.20	.10	1.01	1.15	26.0	1.23	.76	14.50		2.16	15.26	.53
FAGAC69	7970	323.1	326.3	3.2	100	4A10	3.04	.09	.41	.49	15.0	.82	.89	14.10		.90	14.99	.54
FAGA069	7971	352.5	353.9	1.4	100	4LH	3.64	.17	2.40	2.60	33.0	.27	10.48	16.70		5.00	27.18	.52
FAGAG69	7972	353.9	355.2	1.3	100	4LH	3.41	.14	2.50	2.20	32.0	.14	9.09	15.00		4.70	24.09	.47
FAGAG69	7973	234.1	236.0	1.9	100	4A10	3.14	.08	1.81	2.60	34.0	1.23	1.47	11.10		4.41	12.57	.59
FAGUC46	7974	.0	2.4	2.4	71	4D453	3.35	.11	4.90	9.60	94.0	1.17	1.70	14.20		14.50	15.90	.66
FAGUC46	7975	2.4	4.0	1.6	100	4D453	2.98	.06	2.01	2.70	35.0	.62	3.72	5.70		4.71	9.42	.57
FAGUC46	7976	4.0	5.2	1.2	100	4D43	3.26	.10	4.40	7.30	81.0	1.17	1.31	12.20		11.70	13.51	.62
FAGU046	7977	5.2	5.7	.5	100	5D4*	2.92	.03	.30	.85	9.0	.34	4.72	3.17		1.15	7.89	.74
FAGU046	7978	5.7	7.4	1.7	100	4D453	3.20	.05	5.00	9.10	81.0	1.17	2.20	8.50		14.10	10.70	.65
FAGUC46	7979	7.4	10.0	2.6	100	5D4*	2.99	.04	1.02	4.10	19.0	.41	5.98	4.26		5.12	10.24	.80
FAGU046	7980	10.0	10.5	.5	100	4D43	3.38	.01	6.10	10.60	98.0	.89	1.31	13.10		16.70	14.41	.63
FAGUC46	7981	10.5	11.2	.7	100	4A43	3.31	.03	4.40	9.50	76.0	1.03	1.31	13.90		13.90	15.21	.68
FAGUC46	7982	11.2	12.5	1.3	100	4A13	3.55	.02	.59	3.80	15.0	.62	1.64	22.80		4.39	24.44	.87
FAGUC46	7983	14.3	14.7	.4	100	4E0		.02	.13	.21	3.0					.34		.62
FAGU046	7984	14.7	15.7	1.0	100	4K4	3.51	.05	4.90	6.40	80.0	1.85	2.26	11.10		11.30	13.36	.57
FAGUC46	7985	15.7	17.4	1.7	100	4A0		.02	.22	.29	10.0					.51		.57
FAGUC46	7986	41.1	43.5	2.4	87	4A43	3.34	.08	3.20	3.90	52.0	1.17	3.30	11.70		7.10	15.00	.55
FAGUC46	7987	43.5	45.4	1.9	100	4A43	3.38	.10	4.30	3.80	73.0	1.51	1.37	17.00		8.10	18.37	.47
FAGUC46	7988	45.4	46.9	1.5	100	4A43	3.31	.15	4.10	4.10	67.0	1.23	1.51	14.80		8.20	16.31	.50
FAGU046	7989	60.7	61.9	1.2	100	4EG4	4.26	.09	5.70	10.10	90.0	1.03	1.11	19.90		15.80	21.01	.64
FAGU046	7990	61.9	62.4	.5	100	4D4	3.72	.04	8.40	13.70	124.0	1.23	1.68	18.40		22.10	20.08	.62
FAGUC46	7991	62.4	62.9	.5	100	4GE*	4.37	.15	7.10	11.90	117.0	1.71	.96	22.70		19.00	23.66	.63
FAGU046	7992	62.9	64.9	2.0	100	4E4*6	4.50	.17	3.20	5.40	75.0	1.51	.98	38.50		8.60	39.48	.63
FAGU046	7993	64.9	66.8	1.9	100	4GE	4.43	.10	4.80	9.20	77.0	1.30	.60	19.60		14.00	20.20	.66
FAGU046	7994	66.8	68.3	1.5	100	4GE	4.30	.08	4.50	8.30	76.0	1.17	1.00	19.10		12.80	20.10	.65
FAGU046	7995	68.3	69.8	1.5	100	4GE	4.28	.05	4.20	8.30	71.0	1.03	.81	11.50		12.50	12.31	.66
FAGUC46	7996	69.8	70.8	1.0	100	4E4*6	4.80	.11	6.30	12.80	102.0	1.37	1.26	28.00		19.10	29.26	.67
FAGU034	7997	.0	2.1	2.1	52	4L14	2.99	.06	3.50	4.10	45.0	.62	1.72	4.64		7.60	6.36	.54
FAGU034	7998	2.1	4.2	2.1	76	4L14	2.89	.05	1.01	.20	13.0	.41	1.29	3.76		1.21	5.05	.17
FAGU034	7999	4.2	6.3	2.1	95	4L14	2.83	.03	1.27	1.53	17.0	.69	1.12	2.71		2.80	3.83	.55
FAGUC34	8000	6.3	8.3	2.0	100	4L14	2.97	.04	2.30	3.90	32.0	.55	1.29	2.84		6.20	4.13	.63
FAGU126	8001	19.4	20.9	1.5	100	4A41	3.12	.05	3.80	5.70	62.0	1.30	1.09	6.60		9.50	7.69	.60
FAGU126	8002	20.9	22.9	2.0	95	4AE4	3.63	.10	8.40	4.80	104.0	2.26	.99	15.70		13.20	16.69	.36
FAGU126	8003	22.9	24.4	1.5	100	4AE4	3.41	.06	5.00	3.30	55.0	2.06	1.05	14.50		8.30	15.55	.40

FAGU126	8004	24.4	25.9	1.5	100	4AE4	3.60	.18	3.60	3.20	40.0	1.92	1.11	20.00	6.80	21.11	.47
FAGU126	8005	25.9	27.4	1.5	100	4AE4	3.55	.16	7.30	4.10	95.0	2.33	1.03	14.20	11.40	15.23	.36
FAGU126	8006	27.4	28.3	.9	67	4AE4	3.30	.10	5.60	8.40	83.0	1.85	1.32	9.20	14.00	10.52	.60
FAGU126	8007	28.3	30.0	1.7	100	4D4	4.25	.06	5.10	9.70	83.0	1.58	1.39	7.70	14.80	9.09	.66
FAGU126	8008	30.0	31.9	1.9	100	4A4	3.27	.05	4.90	10.20	80.0	1.71	1.47	7.40	15.10	8.87	.68
FAGU126	8009	31.9	33.5	1.6	100	4D45	3.22	.05	3.90	8.20	75.0	1.17	1.43	8.20	12.10	9.63	.68
FAGU126	8010	33.5	35.5	2.0	95	4D45	3.12	.05	4.20	8.40	75.0	.82	1.21	8.47	12.60	9.68	.67
FAGU126	8011	35.5	37.2	1.7	100	4D45	3.25	.03	4.30	7.60	78.0	1.58	1.37	8.80	11.90	10.17	.64
FAGU126	8012	37.2	38.5	1.3	100	4D45	3.26	.03	4.30	7.00	74.0	1.10	1.21	8.80	11.30	10.01	.62
FAGU126	8013	38.5	40.3	1.8	100	4D45	3.31	.05	5.10	8.90	81.0	1.44	1.23	8.60	14.00	9.83	.64
FAGU126	8014	40.3	42.1	1.8	100	4AE4	3.49	.05	4.60	10.10	85.0	2.26	1.60	12.60	14.70	14.20	.69









DDH	SAMPLE	---DEPTHS---	INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAO	PB+ZN	PO+PY	ZN
		FROM TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGU150	8215	47.8 49.5	1.7	88	4G0		.02	2.26	4.80	41.0					7.06		.68
FAGU150	8216	137.5 138.7	1.2	100	4EG4	4.34	.12	6.04	9.30	103.0	1.92	1.41	22.10		15.34	23.51	.61
FAGU150	8217	138.7 139.6	.9	100	4D4	3.90	.04	10.30	20.70	165.0	2.06	2.42	8.40		31.00	10.82	.67
FAGU150	8218	139.6 140.2	.6	50	4D46	3.86	.05	3.70	7.20	52.0	1.17	1.09	15.40		10.90	16.49	.66
FAGU150	8219	140.2 141.6	1.4	100	4E46	4.57	.07	2.20	6.30	37.0	1.51	1.06	28.30		8.50	29.36	.74
FAGU149	8220	.0 4.6	4.6	57	4L14		.04	.64	.89	9.0					1.53		.58
FAGU149	8221	4.6 6.4	1.8	100	4L14	2.92	.03	1.46	.86	14.0	1.51	.66	2.57		2.32	3.23	.37
FAGU149	8222	6.4 9.7	3.3	94	4A1	2.98	.04	1.04	1.74	14.0	1.58	1.22	3.25		2.78	4.47	.63
FAGU149	8223	9.7 12.1	2.4	100	4L14	3.02	.04	.77	1.35	12.0	.62	1.05	2.68		2.12	3.73	.64
FAGU149	8224	12.1 13.0	.9	100	4A1	2.93	.01	.78	2.60	14.0	.27	1.11	.55		3.38	1.66	.77
FAGU149	8225	13.0 14.5	1.5	100	4L14	2.93	.01	.73	1.94	13.0	.21	1.33	2.22		2.67	3.55	.73
FAGU149	8226	14.5 16.1	1.6	100	4L14	2.99	.05	1.68	5.10	31.0	.55	1.04	1.31		6.78	2.35	.75
FAGU149	8227	16.1 18.3	2.2	100	4A1	3.08	.03	.77	2.80	23.0	.82	1.05	7.20		3.57	8.25	.78
FAGU149	8228	18.3 20.4	2.1	100	4A14	3.06	.04	1.48	4.00	35.0	.89	1.19	6.90		5.48	8.09	.73
FAGU149	8229	20.4 22.4	2.0	90	4A14	3.20	.05	3.00	5.40	55.0	.89	2.23	5.70		8.40	7.93	.64
FAGU149	8230	22.4 24.2	1.8	94	4D4	3.28	.05	4.10	9.40	84.0	.96	1.77	9.80		13.50	11.57	.70
FAGU149	8231	24.2 26.0	1.8	94	4D4	3.23	.04	4.60	7.70	77.0	.89	2.37	7.00		12.30	9.37	.63
FAGU149	8233	28.1 30.0	1.9	95	4A0	3.58	.07	1.82	1.45	28.0	1.37	1.21	19.00		3.27	20.21	.44
FAGU149	8234	30.0 31.7	1.7	100	4A4	3.78	.06	6.90	12.70	126.0	1.85	1.25	16.10		19.60	17.35	.65
FAGU149	8235	31.7 33.2	1.5	100	4A4	3.25	.06	3.80	6.50	64.0	1.37	1.33	10.50		10.30	11.83	.63
FAGU149	8236	38.1 41.2	3.1	77	4A1	2.89	.05	1.61	2.50	28.0	.82	1.31	5.00		4.11	6.31	.61
FAGU149	8237	104.5 106.4	1.9	89	4A4	3.20	.09	1.65	3.40	30.0	1.51	1.32	11.00		5.05	12.32	.67
FAGU149	8238	106.4 108.0	1.6	100	4G4	4.29	.29	5.60	8.70	115.0	2.61	1.00	17.50		14.30	18.50	.61
FAGU149	8239	108.0 109.7	1.7	100	4E46	4.45	.17	2.90	3.90	44.0	1.99	1.10	36.40		6.80	37.50	.57
FAGU149	8240	109.7 111.3	1.6	94	4E46	4.78	.16	2.90	3.30	40.0	1.71	1.12	8.40		6.20	9.52	.53
FAGU149	8241	111.3 112.7	1.4	93	4E06	4.49	.23	3.00	1.79	50.0	1.92	1.22	36.00		4.79	37.22	.37
FAGU149	8242	121.0 122.0	1.0	90	4G4	4.47	.12	4.40	7.40	75.0	1.92	2.22	22.50		11.80	24.72	.63
FAGU149	8244	123.0 124.1	1.1	100	4E4	4.42	.14	2.80	3.20	43.0	1.51	2.38	34.60		6.00	36.98	.53
FAGU149	8246	125.3 127.4	2.1	95	4G0	4.25	.09	3.90	5.90	71.0	1.23	1.21	22.30		9.80	23.51	.60
FAGU149	8247	127.4 129.5	2.1	100	4G0	4.50	.13	3.20	5.60	60.0	1.71	.83	25.20		8.80	26.03	.64
FAGU149	8248	129.5 131.6	2.1	100	4G4	4.56	.16	4.70	8.00	94.0	1.71	.84	27.00		12.70	27.84	.63
FAGU149	8249	131.6 133.8	2.2	95	4A0	3.23	.15	1.56	2.70	32.0	1.03	.64	11.30		4.26	11.94	.63
FAGU149	8250	133.8 136.7	2.9	90	4L12	3.05	.08	.43	.78	10.0	.55	1.27	5.60		1.21	6.87	.65
FAGU149	8251	136.7 138.2	1.5	100	4A0	3.28	.09	1.05	1.68	27.0	1.78	.96	39.20		2.73	40.16	.62
FAGU149	8252	138.2 139.5	1.3	92	4G4	4.49	.18	6.30	11.60	124.0	2.26	.44	19.10		17.90	19.54	.65
FAGU149	8253	139.5 141.6	2.1	95	4A0	3.29	.10	1.35	2.05	33.0	.89	.72	15.30		3.40	16.02	.60
FAGU149	8254	144.4 145.2	.8	100	4L4	2.90	.04	1.97	3.00	28.0	.48	1.28	2.10		4.97	3.38	.60
FAGU149	8255	145.2 147.6	2.4	100	4A3	3.17	.12	.35	.47	20.0	.75	.69	14.40		.82	15.09	.57
FAGU149	8256	147.6 149.4	1.8	94	4A4	3.45	.09	5.00	9.90	75.0	1.30	1.17	12.50		14.90	13.67	.66
FAGU149	8257	149.4 150.9	1.5	100	4CD	3.67	.33	1.24	3.30	30.0	1.65	2.63	16.90		4.54	19.53	.73
FAGU149	8258	150.9 152.6	1.7	100	4CD	3.61	.32	1.44	3.90	37.0	1.37	2.07	21.60		5.34	23.67	.73
FAGU149	8259	152.6 154.2	1.6	100	4A3	3.45	.26	.67	.90	25.0	1.37	1.70	12.90		1.57	14.60	.57
FAGU149	8260	154.2 155.4	1.2	100	4CD	3.71	.32	2.40	3.30	42.0	1.71	4.13	11.30		5.70	15.43	.58
FAGU149	8261	180.4 181.6	1.2	100	4G08		.15	4.40	4.80	63.0					9.20		.52
FAGA041	8262	226.5 228.7	2.2	95	4A3	3.53	.21	.56	.50	19.0	1.03	1.38	15.90		1.06	17.28	.47
FAGAC41	8263	228.7 230.9	2.2	100	4A3	3.45	.20	.55	.28	16.0	1.58	1.23	20.10		.83	21.33	.34
FAGA041	8264	230.9 231.8	.9	100	4C3	3.65	.16	1.91	1.34	40.0	1.23	1.96	21.20		3.25	23.16	.41
FAGA041	8265	231.8 232.1	.3	100	4G4	4.63	.03	8.90	12.30	141.0	3.02	1.67	21.50		21.20	23.17	.58
FAGAC41	8266	232.1 233.9	1.8	94	4LH	1.36	.20	.47	.33	16.0	.55	9.30	6.90		.80	16.20	.41
FAGA041	8267	233.9 235.5	1.6	100	4LH	3.04	.22	.37	.36	13.0	.48	12.99	1.89		.73	14.88	.49

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAC	PB+ZN	PO+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGA041	8268	236.0	238.1	2.1	81	4LH		.26	.83	1.04	21.0					1.87		.56
FAGA041	8269	238.1	239.8	1.7	82	4LH		.28	.48	.42	19.0					.90		.47
FAGA041	827C	241.3	243.2	1.9		4LO		.20	.46	.27	13.0					.73		.37
FAGA041	8271	256.2	257.3	1.1	100	4H1#	3.14	.13	.27	.14	12.0	2.19	15.71	4.03		.41	19.74	.34
FAGA041	8272	257.3	258.1	.8	100	5A6	2.84	.03	.04	.03	3.0	.48	3.35	.84		.07	4.19	.42
FAGA041	8273	258.1	259.5	1.4	93	4CEH	3.64	.34	.40	.45	18.0	1.17	9.74	15.60		.85	25.34	.53
FAGA041	8274	259.5	260.7	1.2	100	4G4#8	4.07	.14	6.10	8.00	77.0	1.51	1.43	16.90		14.10	18.33	.57
FAGA041	8275	260.7	261.3	.6	83	4C0	3.26	.09	1.45	1.16	28.0	.96	3.74	10.60		2.61	14.34	.44
FAGA041	8276	261.3	264.0	2.7	100	4A3	3.32	.19	.37	.49	11.0	1.03	1.69	16.60		.86	18.29	.57
FAGA041	8277	264.0	265.9	1.9	100	4E8	4.35	.23	2.20	1.69	43.0	1.78	3.03	31.90		3.89	34.93	.43
FAGA041	8278	265.9	266.6	.7	86	4A1	3.16	.08	.49	.52	15.0	.41	7.08	4.58		1.01	11.66	.52
FAGA041	8279	279.0	281.4	2.4	100	4CE7	3.49	.22	1.56	1.45	25.0	2.19	.88	6.73		3.01	7.61	.48
FAGA041	8280	281.4	282.2	.8	88	4E14	4.23	.13	3.70	4.20	65.0	1.44	2.24	23.50		7.90	25.74	.53
FAGA041	8281	282.2	283.2	1.0	100	4A0	3.50	.18	1.30	1.18	32.0	1.23	2.21	18.80		2.48	21.01	.48
FAGA041	8282	283.2	284.0	.8	100	4E84	4.23	.12	2.70	3.60	54.0	1.17	3.62	27.50		6.30	31.12	.57
FAGA041	8283	284.0	285.1	1.1	100	4E1*8	3.50	.25	.70	.27	20.0	.89	7.35	16.00		.97	23.35	.28
FAGA041	8284	285.1	286.3	1.2	100	5B29	2.97	.05	.17	.18	10.0	1.03	4.30	2.12		.35	6.42	.51
FAGA041	8285	286.3	287.9	1.6	100	4E18*	3.34	.17	.53	.33	18.0	.69	11.44	9.60		.86	21.04	.38
FAGA041	8286	287.9	288.8	.9	100	5B2		.06	.05	.07	9.0					.12		.58
FAGA041	8287	288.8	289.3	.5	80	4E*81		.23	1.60	1.48	28.0					3.08		.48
FAGA076	8288	113.1	114.0	.9	100	4D0	3.08	.04	1.84	3.60	23.0	.48	4.41	5.80		5.44	10.21	.66
FAGA076	8289	114.8	116.0	1.2	42	4C0	3.29	.04	1.23	2.40	26.0	.62	8.20	7.60		3.63	15.80	.66
FAGA076	829C	144.1	145.9	1.8	100	4A4	3.25	.04	2.30	4.00	33.0	.82	1.22	9.60		6.30	10.82	.63
FAGA076	8291	145.9	147.8	1.9	95	4A4	3.14	.05	2.60	2.80	35.0	.48	1.13	8.60		5.40	9.73	.52
FAGA076	8292	147.8	149.3	1.5	93	4A4	3.01	.04	1.99	2.30	30.0	.41	1.62	4.02		4.29	5.64	.54
FAGA076	8293	251.3	252.8	1.5	100	4D4*	3.80	.06	9.60	14.20	175.0	.62	3.19	9.10		23.80	12.29	.60
FAGA076	8294	264.7	265.5	.8	88	4A4		.04	1.76	3.80	44.0					5.56		.68
FAGA076	8295	275.1	276.2	1.1	73	4A4		.02	2.40	6.20	52.0					8.60		.72
FAGA076	8296	280.8	281.4	.6	83	4A01		.08	1.42	2.30	32.0					3.72		.62
FAGA076	8297	281.8	283.1	1.3	100	4A01		.04	1.53	1.58	30.0					3.11		.51
FAGA076	8298	292.8	293.6	.8	88	4G4		.16	8.80	14.10	138.0					22.90		.62
FAGA076	8299	366.5	367.8	1.3	100	4A4L		.02	.74	1.36	19.0					2.10		.65
FAGA035	830C	158.8	160.3	1.5	100	4E4	4.73	.18	3.40	2.50	61.0	2.74	1.94	2.06		5.90	4.00	.42
FAGA163	8301	109.4	110.3	.9	89	4E14	4.40	.12	5.60	8.70	130.0	1.44	1.25	28.70		14.30	29.95	.61
FAGA163	8302	110.3	112.4	2.1	95	4A4	3.27	.03	3.00	4.60	65.0	1.78	1.53	9.10		7.60	10.63	.61
FAGA163	8303	85.5	86.2	.7	86	4A4		.02	3.30	8.20	70.0					11.50		.71
FAGA032	8304	156.4	158.9	2.5	100	4E184	3.80	.19	3.00	4.00	46.0	.41	8.62	15.50		7.00	24.12	.57
FAGA032	8305	242.9	244.6	1.7	100	4DEG	4.21	.19	4.90	7.70	120.0	1.37	1.17	23.60		12.60	24.77	.61
FAGA032	8306	284.1	285.3	1.2	100	4A0	3.04	.05	1.72	3.20	36.0	.55	3.84	5.50		4.92	9.34	.65
FAGA032	8307	285.3	286.2	.9	100	4E46	4.56	.28	4.70	5.40	82.0	1.92	1.00	28.30		10.10	29.30	.53
FAGA032	8308	286.2	288.0	1.8	94	4C5	3.40	.13	.67	.92	20.0	.62	4.70	15.20		1.59	19.90	.58
FAGA032	8309	288.0	289.9	1.9	95	4C5	3.51	.22	1.11	1.22	25.0	.82	6.72	16.50		2.33	23.22	.52
FAGA032	8310	289.9	292.2	2.3	100	4C5	3.40	.15	.93	1.28	20.0	.41	6.25	14.10		2.21	20.35	.58
FAGA032	8311	292.2	293.8	1.6	100	4A0	3.24	.14	.16	.36	10.0	.34	3.77	13.70		.52	17.47	.69
FAGA032	8312	293.8	295.7	1.9	95	4CAE	3.82	.21	1.72	1.74	33.0	.75	5.58	20.70		3.46	26.28	.50
FAGA032	8313	295.7	297.8	2.1	100	4CAE	3.41	.15	.85	.76	23.0	.75	3.29	15.60		1.61	18.89	.47
FAGA032	8314	297.8	299.8	2.0	100	4A0	3.28	.18	.32	.79	16.0	.75	2.74	13.30		1.11	16.04	.71
FAGA032	8315	299.8	301.3	1.5	100	4C8	3.40	.19	1.24	1.59	24.0	1.58	8.63	11.90		2.83	20.53	.56
FAGA032	8316	301.3	302.8	1.5	100	4C8	3.77	.19	1.73	2.06	32.0	.82	4.90	17.70		3.79	22.60	.54
FAGA032	8317	302.8	304.8	2.0	100	4A0	3.65	.18	.11	.33	10.0	.96	3.56	9.80		.44	13.36	.75

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAO	PB+ZN	PC+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGA032	8318	304.8	306.6	1.8	100	4A0	3.24	.14	.17	.31	13.0	.82	3.18	11.40		.48	14.58	.65
FAGA032	8319	306.6	308.5	1.9	95	4A0		.14	.11	.40	10.0					.51		.78
FAGA032	8320	308.5	310.3	1.8	100	4A0		.17	.11	.22	9.0					.33		.67
FAGA032	8321	310.3	312.1	1.8	100	4A0		.17	.12	.34	8.0					.46		.74
FAGA032	8322	312.1	313.9	1.8	100	4A0		.11	.11	.33	8.0					.44		.75
FAGA032	8323	313.9	315.8	1.9	95	4A0		.14	.12	.68	9.0					.80		.85
FAGA032	8324	315.8	317.6	1.8	100	4A0		.15	.15	.71	10.0					.86		.83
FAGA032	8325	317.6	319.4	1.8	100	4A0		.16	.20	.24	14.0					.44		.54
FAGA032	8326	319.4	321.3	1.9	95	4A0		.15	.13	.63	10.0					.76		.83
FAGA032	8327	321.3	323.1	1.8	100	4A0		.12	.17	.58	9.0					.75		.77
FAGA032	8328	323.1	324.9	1.8	100	4A0		.23	.10	.14	9.0					.24		.58
FAGA032	8329	324.9	326.7	1.8	100	4A0		.14	.69	1.01	16.0					1.70		.59
FAGAG32	8330	326.7	328.1	1.4	93	4A0		.06	.73	1.07	17.0					1.80		.59
FAGA032	8331	328.1	329.9	1.8	100	4AE		.13	1.16	1.04	27.0					2.20		.47
FAGA160	8332	49.2	51.5	2.3	96	4A0	2.99	.01	1.39	3.10	29.0	.48	.86	5.40		4.49	6.26	.69
FAGA160	8333	51.5	54.0	2.5	60	4A0	2.95	.01	1.56	5.00	39.0	.55	.86	5.10		6.56	5.96	.76
FAGA160	8334	54.0	56.1	2.1	48	4A0	3.11	.01	2.07	5.70	47.0	.75	1.34	8.40		7.77	9.74	.73
FAGA160	8335	65.9	68.0	2.1	95	4A0	3.15	.03	2.50	5.70	43.0	.75	3.01	8.60		8.20	11.61	.70
FAGA160	8336	68.0	70.2	2.2	100	4DA4	3.16	.04	2.80	4.80	50.0	.89	2.41	8.40		7.60	10.81	.63
FAGA160	8337	71.3	73.5	2.2	95	4A4	3.18	.02	4.10	9.40	80.0	.75	1.52	12.70		13.50	14.22	.70
FAGA160	8338	73.5	75.7	2.2	100	4A4	3.10	.04	3.90	5.40	65.0	.75	2.11	7.10		9.30	9.21	.58
FAGA160	8339	79.2	81.1	1.9	95	4C0		.07	.94	1.22	19.0					2.16		.57
FAGA160	8340	84.3	86.0	1.7	94	4C0	2.89	.04	1.08	1.71	20.0	.48	2.24	2.69		2.79	4.93	.61
FAGA160	8341	86.0	87.8	1.8	89	4C0	2.95	.05	.99	1.11	19.0	.69	2.28	3.75		2.10	6.03	.53
FAGA160	8342	88.6	90.3	1.7	100	4B0	2.89	.04	.73	.88	18.0	.27	2.77	2.59		1.61	5.36	.55
FAGA160	8343	95.6	97.5	1.9	100	4A4	2.99	.02	1.70	5.10	28.0	.27	3.82	1.69		6.80	5.51	.75
FAGA160	8344	97.5	99.5	2.0	50	4A0	2.88	.02	1.01	2.30	17.0	.27	3.39	1.35		3.31	4.74	.69
FAGA160	8345	99.5	101.5	2.0	60	4A4	2.94	.02	1.81	4.00	30.0	.34	1.81	3.55		5.81	5.36	.69
FAGA160	8346	101.5	102.1	.6	100	4ED	3.66	.06	1.97	5.20	34.0	.48	2.15	22.10		7.17	24.25	.73
FAGA160	8347	108.6	110.0	1.4		4A0	2.99	.02	1.38	3.20	27.0	.55	.91	5.05		4.58	5.96	.70
FAGA160	8348	110.0	112.0	2.0	100	4A0	2.95	.05	1.84	2.90	35.0	1.03	.63	13.50		4.74	14.13	.61
FAGA160	8349	112.0	113.7	1.7	94	4A0	3.14	.05	.47	1.02	12.0	.48	.51	11.30		1.49	11.81	.69
FAGA160	8350	116.8	118.3	1.5	100	4L4		.04	.60	.49	10.0					1.09		.45
FAGA160	8351	118.3	119.8	1.5	73	4L4		.08	.51	.77	12.0					1.28		.60
FAGA160	8352	120.6	121.8	1.2	100	4D0	3.02	.03	1.85	3.80	25.0	.21	2.45	2.15		5.65	4.60	.67
FAGA160	8353	121.8	123.4	1.6	100	4H14	3.55	.08	2.90	6.50	58.0	.41	13.90	8.40		9.40	22.30	.69
FAGA160	8354	123.4	125.2	1.8	100	4D0	2.52	.10	3.30	5.00	60.0	1.03	2.77	9.70		8.30	12.47	.60
FAGA160	8355	125.2	126.9	1.7	100	4D0	3.11	.05	3.20	5.70	55.0	.55	3.25	5.10		8.90	8.35	.64
FAGA160	8356	129.4	130.8	1.4	100	4D0	3.05	.03	1.98	4.60	33.0	.48	3.39	3.14		6.58	6.53	.70
FAGA160	8357	130.8	132.0	1.2	83	4A4	2.88	.03	1.50	3.90	23.0	.27	1.15	.89		5.40	2.04	.72
FAGA160	8358	132.0	134.1	2.1	76	4D0	3.53	.07	3.20	5.60	46.0	.41	5.48	9.80		8.80	15.28	.64
FAGA069	8359	138.6	139.1	.5	100	4C0		.19	.77	1.05	24.0					1.82		.58
FAGA069	8360	139.1	140.1	1.0	100	4A3	3.59	.15	.35	.37	13.0	.69	1.90	22.60		.72	24.50	.51
FAGAG69	8361	140.1	140.7	.6	83	4D4	3.92	.24	6.30	5.10	100.0	2.06	2.42	20.90		11.40	23.32	.45
FAGA069	8362	140.7	142.5	1.8	94	4C3	4.02	.25	.47	.55	23.0	1.44	2.89	29.30		1.02	32.19	.54
FAGA069	8363	142.5	143.9	1.4	86	4A3	3.50	.11	1.07	1.54	28.0	1.58	1.60	19.70		2.61	21.30	.59
FAGA069	8364	144.3	146.6	2.3	96	4A4	3.41	.08	3.90	6.00	68.0	1.58	1.14	12.90		9.90	14.04	.61
FAGA069	8365	146.6	148.3	1.7	100	4A4	3.77	.19	2.50	4.90	45.0	1.37	1.42	16.80		7.40	18.22	.66
FAGAG69	8366	148.3	149.4	1.1	91	4A0	3.43	.11	1.10	1.90	27.0	1.71	.79	17.20		3.00	17.99	.63
FAGA069	8367	149.4	151.2	1.8	100	4A4	3.24	.04	1.98	3.50	37.0	.82	.93	9.20		5.48	10.13	.64

DDH	SAMPLE	---DEPTHS---		INT M	REC %	ROCK UNIT	S.G.	CU %	PB %	ZN %	AG G/MT	AU G/MT	PO %	FY %	BAO %	PB+ZN %	PC+PY %	ZN RATIO
		FROM	TO															
FAGA069	8368	151.2	153.0	1.8	100	4L0	2.97	.02	.32	.60	6.0	.55	1.18	1.78		.92	2.96	.65
FAGA069	8369	153.0	154.8	1.8	100	4A10	2.98	.03	.69	.48	11.0	.69	.79	5.27		1.17	6.06	.41
FAGA069	8370	154.8	157.1	2.3	96	4A10	2.94	.04	.59	.59	8.0	.75	.64	5.21		1.18	5.85	.50
FAGA069	8371	157.1	159.1	2.0	100	4A10	2.93	.03	.94	1.79	18.0	.69	.85	1.10		2.73	1.95	.66
FAGA069	8372	159.1	160.8	1.7	94	4L4	3.04	.04	1.62	2.00	28.0	.69	1.13	2.90		3.62	4.03	.55
FAGA069	8373	162.2	162.7	.5	100	4L24		.23	.39	1.26	9.0					1.65		.76
FAGAC69	8374	162.7	164.8	2.1	100	4A10		.13	.80	1.70	20.0					2.50		.68
FAGAC69	8375	164.8	166.7	1.9	100	4A10		.09	.25	.48	6.0					.73		.66
FAGAC69	8376	166.7	168.4	1.7	100	4A10		.09	.41	.90	8.0					1.31		.69
FAGAC69	8377	168.4	168.9	.5	80	5C4*	3.12	.02	1.44	5.70	23.0	.41	4.51	2.17		7.14	6.68	.80
FAGA069	8378	168.9	170.0	1.1	100	4A14	3.38	.04	1.84	4.60	34.0	1.10	1.55	12.00		6.44	13.55	.71
FAGA069	8379	170.0	170.7	.7	100	4L24	3.27	.05	.46	1.03	9.0	.34	3.72	5.12		1.49	8.84	.69
FAGA069	8380	172.2	174.0	1.8	100	4A14	3.28	.10	2.40	4.40	39.0	1.03	1.85	8.20		6.80	10.05	.65
FAGA069	8381	174.0	175.9	1.9	95	4A10	3.13	.10	1.74	1.90	29.0	.96	1.01	5.70		3.64	6.71	.52
FAGA069	8382	175.9	177.5	1.6	100	4A10	3.11	.06	1.14	1.87	22.0	.75	.93	5.60		3.01	6.53	.62
FAGA069	8383	177.5	179.3	1.8	94	4A14	3.11	.02	1.95	4.80	38.0	.55	1.16	.66		6.75	1.82	.71
FAGA069	8384	179.3	181.1	1.8	100	4A10	2.96	.03	1.46	3.00	28.0	.41	.85	.32		4.46	1.17	.67
FAGA069	8385	181.1	183.5	2.4	75	4A10	3.08	.02	1.41	2.60	25.0	.41	.97	.71		4.01	1.68	.65
FAGA069	8386	183.5	184.8	1.3	100	4A10	2.98	.02	1.36	2.05	21.0	.82	.72	1.20		3.41	1.92	.60
FAGA069	8387	184.8	186.8	2.0	90	4A10	2.98	.03	.45	1.17	6.0	.41	.98	.40		1.62	1.38	.72
FAGAC69	8388	186.8	188.7	1.9	95	4A10	2.84	.04	1.84	3.10	31.0	.69	1.16	2.56		4.94	3.72	.63
FAGA069	8389	188.7	190.2	1.5	100	4A14	3.13	.03	1.71	4.00	36.0	.41	.93	2.23		5.71	3.16	.70
FAGA069	8390	190.2	191.7	1.5	100	4A14	3.00	.02	1.74	3.30	28.0	.34	1.00	.99		5.04	1.99	.65
FAGA069	8391	191.7	193.8	2.1	86	4A10	2.97	.02	1.05	2.02	18.0	.41	.87	.43		3.07	1.30	.66
FAGA069	8392	193.8	196.2	2.4	92	4A10	2.99	.02	1.32	2.80	24.0	.27	1.20	.55		4.12	1.75	.68
FAGAC69	8393	196.2	198.1	1.9	100	4A14	3.01	.03	1.77	3.60	32.0	1.17	1.05	.43		5.37	1.48	.67
FAGA069	8394	198.1	200.2	2.1	95	4A10	3.05	.03	1.39	3.10	30.0	.82	.91	.70		4.49	1.61	.69
FAGA069	8395	200.2	202.1	1.9	100	4A10	3.17	.02	1.14	3.70	23.0	.62	.95	2.28		4.84	3.23	.76
FAGA069	8396	202.1	204.1	2.0	100	4A10	2.98	.02	1.38	3.30	29.0	.55	.81	1.79		4.68	2.60	.71
FAGA069	8397	204.1	205.7	1.6	100	4A10	3.27	.03	.61	1.83	23.0	.89	1.03	12.80		2.44	13.83	.75
FAGA069	8398	205.7	207.3	1.6	100	4A10	3.20	.02	.94	2.90	32.0	.89	1.48	10.52		3.84	12.00	.76
FAGAC69	8399	209.2	211.2	2.0	100	4CD	3.50	.05	1.55	2.30	32.0	1.10	1.52	16.20		3.85	17.72	.60
FAGA069	8400	211.2	213.2	2.0	100	4D45	3.42	.04	4.60	8.90	81.0	1.30	1.50	10.20		13.50	11.70	.66
FAGU156	8401	2.9	6.1	3.2	100	4L24	2.97	.08	2.40	3.00	36.0	.62	.91	.77		5.40	1.68	.56
FAGU156	8402	6.1	7.2	1.1	73	5D4*9	2.91	.01	.69	.99	12.0	.21	2.47	.04		1.68	2.51	.59
FAGU156	8403	7.2	9.1	1.9	100	4L14	3.04	.05	1.02	1.90	17.0	.62	1.21	2.80		2.92	4.01	.65
FAGU156	8404	15.2	17.4	2.2	86	4A1	2.93	.05	1.31	1.57	24.0	.96	1.72	1.28		2.88	3.00	.55
FAGU156	8405	17.4	19.7	2.3	100	4A1	3.02	.08	2.09	1.72	41.0	.69	2.17	3.10		3.81	5.27	.45
FAGU156	8406	47.3	48.7	1.4	79	4L1	2.98	.09	.29	.38	7.0	2.40	2.78	4.52		.67	7.30	.57
FAGU156	8407	48.7	51.0	2.3	100	4A4	3.73	.27	2.60	3.40	42.0	1.65	.99	7.30		6.00	8.29	.57
FAGU156	8408	51.0	53.2	2.2	100	4A0	3.57	.18	1.14	1.20	36.0	1.03	1.23	21.60		2.34	22.83	.51
FAGU156	8409	53.2	55.2	2.0	95	4E46*	4.61	.21	3.30	4.90	58.0	1.58	1.27	34.30		8.20	35.57	.60
FAGU156	8410	55.2	57.0	1.8	78	4E46*	4.76	.23	6.80	7.80	87.0	1.58	1.49	30.10		14.60	31.59	.53
FAGU156	8411	57.0	59.0	2.0	100	4K4	4.21	.30	5.10	7.70	96.0	1.58	2.30	23.20		12.80	25.50	.60
FAGU156	8412	59.0	62.1	3.1	100	4G4*	4.64	.15	4.50	8.40	82.0	1.37	.85	21.70		12.90	22.55	.65
FAGU156	8413	62.1	63.9	1.8	100	4EG4	4.61	.25	4.70	7.30	97.0	1.58	1.01	29.10		12.00	30.11	.61
FAGU154	8415	1.2	2.9	1.7	100	4A4	3.06	.05	2.70	6.00	41.0	.62	1.31	6.50		8.70	7.81	.69
FAGU154	8416	2.9	4.6	1.7	100	4A4	3.16	.07	3.10	5.10	50.0	1.58	1.22	9.18		8.20	10.40	.62
FAGU154	8417	4.6	6.4	1.8	100	4A4	3.69	.17	5.30	10.90	96.0	1.51	1.63	16.10		16.20	17.73	.67
FAGU154	8418	6.4	7.1	.7	86	4E4	4.47	.01	9.60	15.30	161.0	1.10	1.29	24.40		24.90	25.69	.61

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	SAO	PB+ZN	PC+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGU154	8419	7.1	8.8	1.7	100	4A4	3.27	.05	3.00	6.60	51.0	1.03	1.19	11.40		9.60	12.59	.69
FAGU154	8420	8.8	10.6	1.8	100	4A4	3.02	.02	1.58	3.80	31.0	.41	.94	6.10		5.38	7.04	.71
FAGU154	8421	10.6	12.4	1.8	100	4A4	3.22	.03	2.40	5.60	41.0	.48	2.05	9.80		8.00	11.85	.70
FAGU154	8422	12.4	14.2	1.8	100	4A4	3.29	.07	3.30	6.80	58.0	.69	1.49	12.00		10.10	13.49	.67
FAGU154	8423	14.2	15.3	1.1	100	4A4	3.39	.10	4.40	11.10	74.0	.75	2.48	9.60		15.50	12.08	.72
FAGU154	8424	15.3	16.5	1.2	92	4A0	3.42	.10	.82	2.70	25.0	1.17	1.08	17.90		3.52	18.98	.77
FAGU154	8425	16.5	17.8	1.3	100	4A4	3.36	.09	4.10	8.70	75.0	.82	2.24	11.50		12.80	13.74	.68
FAGU154	8426	17.8	18.8	1.0	100	5D6	2.93	.01	.26	.16	6.0	.21	5.29	3.71		.42	9.00	.38
FAGU154	8427	18.8	20.8	2.0	100	4A4	3.06	.03	2.50	5.40	47.0	.69	2.20	5.20		7.90	7.40	.68
FAGU154	8428	20.8	22.8	2.0	100	4A4	3.34	.14	5.10	8.40	94.0	1.03	1.32	8.00		13.50	9.32	.62
FAGU154	8429	22.8	24.8	2.0	100	4A0	3.50	.20	1.58	1.91	38.0	1.78	1.10	18.30		3.49	19.40	.55
FAGU154	8430	24.8	26.8	2.0	100	4A4	3.53	.20	3.20	5.30	69.0	1.64	1.45	16.30		8.50	17.75	.62
FAGU144	8431	57.3	57.9	.6	100	4B4	2.93	.01	2.60	5.90	42.0	.69	2.40	1.02		8.50	3.42	.69
FAGU144	8432	57.9	59.4	1.5	100	4A34	3.27	.05	3.60	7.80	61.0	.82	2.88	28.30		11.40	31.18	.68
FAGU144	8433	59.4	61.0	1.6	75	4A34	3.50	.07	4.10	6.10	72.0	1.92	2.13	15.30		10.20	17.43	.60
FAGU144	8434	61.0	61.2	.2	100	4H14	3.93	.05	5.70	7.30	96.0	1.10	21.54	8.90		13.00	30.44	.56
FAGU144	8435	64.1	65.9	1.8	100	4A14	2.98	.02	1.89	3.50	32.0	.96	1.50	8.50		5.39	10.00	.65
FAGU135	8436	.0	3.5	3.5	94	4A4	3.30	.02	4.10	7.80	70.0	1.03	2.19	10.20		11.90	12.39	.66
FAGU135	8437	43.7	45.7	2.0	100	4AD4	3.63	.17	5.90	11.30	159.0	2.19	1.52	11.70		17.20	13.22	.66
FAGU135	8438	45.7	48.2	2.5	96	4AD4	3.56	.06	5.00	7.80	83.0	1.92	1.42	34.00		12.80	35.42	.61
FAGU135	8439	49.6	49.9	.3	100	4A0	3.80	.05	.17	.14	12.0	.55	15.09	10.00		.31	25.09	.45
FAGU135	8440	49.9	51.8	1.9	100	4CAE	3.98	.09	.19	.09	22.0	2.33	1.77	9.10		.28	10.87	.32
FAGU135	8441	55.1	56.9	1.8	100	4A41	3.28	.06	3.40	5.00	66.0	2.06	1.07	7.70		8.40	8.77	.60
FAGU135	8442	56.9	58.6	1.7	100	4A41	3.16	.04	3.20	4.70	55.0	1.65	.91	11.20		7.90	12.11	.59
FAGU135	8443	58.6	60.5	1.9	100	4A41	3.38	.04	3.60	6.80	77.0	1.51	1.70	11.90		10.40	13.60	.65
FAGU135	8444	60.5	62.5	2.0	100	4A41	3.42	.09	3.90	5.50	72.0	1.92	1.70	6.10		9.40	7.80	.59
FAGU135	8445	64.5	67.3	2.8	100	4A1	3.06	.05	1.19	2.05	19.0	.69	1.30	4.70		3.24	6.00	.63
FAGU135	8446	68.9	70.6	1.7	100	4A1	3.00	.04	.90	1.90	13.0	.69	1.18	5.50		2.80	6.68	.68
FAGU135	8447	70.6	72.0	1.4	100	4A1	3.06	.08	1.19	1.68	19.0	1.23	1.27	2.92		2.87	4.19	.59
FAGU135	8448	72.0	74.3	2.3	100	4L21	2.94	.03	.26	.46	6.0	.27	1.24	.66		.72	1.90	.64
FAGU135	8449	82.1	83.8	1.7	100	4L21		.03	1.08	2.60	20.0					3.68		.71
FAGU135	8450	83.8	85.3	1.5	100	4A1		.02	.46	.86	7.0					1.32		.65
FAGU135	8451	85.3	86.9	1.6	100	4A1		.04	.53	1.50	6.0					2.03		.74
FAGU135	8452	105.2	106.5	1.3	100	4A0	3.22	.06	1.22	1.67	22.0	.75	4.75	8.50		2.89	13.25	.58
FAGU135	8453	106.5	109.7	3.2	47	4G4	3.79	.18	4.40	7.60	85.0	1.99	1.45	21.60		12.00	23.05	.63
FAGU135	8454	109.7	111.3	1.6	25	4C0	3.11	.06	.29	.55	6.0	.34	1.46	11.90		.84	13.36	.66
FAGU135	8455	133.8	134.1	.3	100	4A0	3.18	.08	.32	.54	8.0	.62	3.39	11.20		.86	14.59	.63
FAGU135	8456	134.1	135.6	1.5	100	4E4	4.19	.10	6.00	7.90	90.0	2.40	1.80	25.80		13.90	27.60	.57
FAGU135	8457	135.6	137.2	1.6	94	4E4	4.54	.09	3.80	6.70	68.0	1.37	1.18	32.30		10.50	33.48	.64
FAGU135	8458	137.2	139.1	1.9	100	4A4	3.20	.12	1.64	3.70	31.0	.89	1.76	9.20		5.34	10.96	.69
FAGU135	8459	139.1	140.8	1.7	100	4A0	2.97	.09	.09	.16	2.0	.34	2.26	5.10		.25	7.36	.64
FAGU135	8460	140.8	142.4	1.6	37	4A0	3.00	.14	.47	.69	8.0	.62	1.28	6.20		1.16	7.48	.59
FAGU135	8461	142.4	143.3	.9	100	4AE4	4.08	.07	2.20	3.90	37.0	.82	1.84	18.60		6.10	20.44	.64
FAGU135	8462	143.3	144.6	1.3	100	4AE	3.42	.10	1.03	1.31	21.0	.69	2.49	14.40		2.34	16.89	.56
FAGU135	8463	170.1	172.0	1.9	84	4A4	3.34	.05	2.50	3.90	34.0	.62	1.58	10.30		6.40	11.88	.61
FAGU135	8464	172.0	174.0	2.0	100	4G4	4.31	.12	5.40	8.40	91.0	1.37	1.24	15.80		13.80	17.04	.61
FAGU135	8465	174.0	176.0	2.0	100	4E84	4.47	.22	2.80	3.00	35.0	1.17	3.95	31.50		5.80	35.45	.52
FAGU135	8466	176.0	177.8	1.8	100	4E8	4.42	.25	1.81	2.40	27.0	2.67	5.37	32.80		4.21	38.17	.57
FAGU135	8467	177.8	179.7	1.9	100	4E8	3.93	.20	2.70	1.83	26.0	1.51	5.65	23.70		4.53	29.35	.40
FAGU135	8468	179.7	181.8	2.1	100	4E84	4.51	.27	2.90	2.60	45.0	1.58	6.79	30.90		5.50	37.69	.47

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAO	PB+ZN	PC+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGU135	8469	181.8	182.1	.3	100	4G4	4.40	.14	6.40	8.30	86.0	2.19	1.77	13.00		14.70	14.77	.56
FAGU135	847C	182.1	183.1	1.0	100	4E8	4.64	.24	1.11	.46	25.0	2.67	3.18	38.20		1.57	41.38	.29
FAGU135	8471	183.1	183.7	.6	100	4G0*	4.21	.16	5.70	4.20	72.0	1.85	4.12	19.50		9.90	23.62	.42
FAGU135	8472	183.7	184.4	.7	100	4E7	4.29	.40	1.83	1.96	32.0	1.10	7.62	29.40		3.79	37.02	.52
FAGU135	8473	184.4	185.5	1.1	100	4A0	3.23	.07	1.63	1.69	28.0	.55	3.68	9.40		3.32	13.08	.51
FAGA163	8474	26.0	28.0	2.0	100	4A12	3.09	.05	2.70	2.30	39.0	.41	.99	6.00		5.00	6.99	.46
FAGA163	8475	28.0	29.9	1.9	89	4A14	3.17	.02	3.60	4.50	40.0	.34	1.32	7.10		8.10	8.42	.56
FAGA163	8476	29.9	34.6	4.7	34	4B4	3.01	.03	1.67	3.50	34.0	.69	1.05	4.45		5.17	5.50	.68
FAGA163	8477	34.6	36.1	1.5	100	4B4	2.89	.02	1.47	4.90	37.0	.07	1.47	.36		6.37	1.83	.77
FAGA163	8478	36.1	38.0	1.9	100	4A14	2.96	.03	1.68	3.60	36.0	.27	1.63	3.17		5.28	4.80	.68
FAGA163	8479	38.0	39.8	1.8	100	4A4	2.98	.03	1.91	4.40	36.0	.27	2.09	2.22		6.31	4.31	.70
FAGA163	848C	39.8	41.5	1.7	94	4A4	2.93	.02	1.92	3.60	31.0	.34	1.41	2.00		5.52	3.41	.65
FAGA163	8481	41.5	43.0	1.5	100	4A4	3.06	.04	3.70	6.80	45.0	.82	3.25	3.47		10.50	6.72	.65
FAGA163	8482	50.4	53.9	3.5	86	4A14	2.96	.04	3.00	5.70	47.0	.69	2.15	2.20		8.70	4.35	.66
FAGA163	8483	53.9	55.6	1.7	94	4A4	2.96	.04	1.69	3.60	24.0	1.30	1.85	4.24		5.29	6.09	.68
FAGA163	8484	66.4	68.4	2.0	85	4A41	3.16	.02	3.30	7.00	55.0	1.03	2.99	6.00		10.30	8.99	.68
FAGA163	8485	68.4	70.2	1.8	100	4A4	3.16	.02	1.86	4.90	33.0	.89	1.90	6.60		6.76	8.50	.72
FAGA163	8486	70.2	71.8	1.6	100	4A0	3.08	.02	.83	1.81	20.0	.75	1.59	5.80		2.64	7.39	.69
FAGA163	8487	71.8	73.7	1.9	100	4E4	3.82	.08	7.80	1.54	139.0	1.65	4.39	11.60		9.34	15.99	.16
FAGA163	8488	73.7	75.3	1.6	100	5D0	3.21	.02	1.29	3.70	31.0	.41	4.94	6.10		4.99	11.04	.74
FAGA163	8489	75.3	76.8	1.5	100	4E10	3.53	.02	1.21	3.30	27.0	.75	2.62	17.10		4.51	19.72	.73
FAGA163	849C	76.8	79.0	2.2	100	4D4	3.42	.12	3.70	9.80	68.0	1.10	2.51	10.00		13.50	12.51	.73
FAGA163	8491	91.4	93.3	1.9	100	4A0	3.15	.02	1.08	2.90	21.0	.69	1.16	7.60		3.98	8.76	.73
FAGA163	8492	93.3	95.4	2.1	100	4A34	3.20	.05	1.74	3.30	34.0	.82	1.67	9.40		5.04	11.07	.65
FAGA163	8493	95.4	96.6	1.2	100	4A0	3.08	.04	.92	1.25	18.0	1.17	1.01	7.90		2.17	8.91	.58
FAGA163	8494	96.6	98.3	1.7	100	4A0	3.09	.04	.91	1.40	19.0	.89	1.07	6.50		2.31	7.57	.61
FAGA163	8495	98.3	99.8	1.5	100	5D4	3.23	.06	3.20	4.70	53.0	1.03	4.12	4.00		7.90	8.18	.59
FAGA163	8496	99.8	102.6	2.8	100	4A0	3.09	.03	.52	.97	14.0	.96	1.15	6.80		1.49	7.95	.65
FAGA163	8497	102.6	103.6	1.0	100	5D4	3.06	.02	.35	.71	9.0	.27	5.23	1.26		1.06	6.49	.67
FAGA163	8498	103.6	104.2	.6	83	4D4	3.92	.09	8.60	20.40	148.0	2.54	4.57	10.60		29.00	15.17	.70
FAGA163	8499	104.2	107.3	3.1	52	4A4	3.01	.05	1.44	4.20	28.0	2.33	2.83	2.31		5.64	5.14	.74
FAGA163	850C	108.5	109.4	.9	89	4A14	3.37	.07	2.60	4.70	41.0	1.03	1.86	12.20		7.30	14.06	.64
FAGU146	8501	15.2	17.2	2.0	95	4A0	3.19	.06	1.36	2.64	30.0	.75	.69	11.40		4.00	12.09	.66
FAGU146	8502	17.2	19.2	2.0	100	4A0	3.18	.08	.92	1.51	26.0	.89	.61	11.80		2.43	12.41	.62
FAGU146	8503	19.2	21.2	2.0	100	4A0	3.22	.05	.98	1.43	26.0	.82	.65	13.40		2.41	14.05	.59
FAGU146	8504	21.2	23.2	2.0	100	4A0	3.08	.05	1.13	1.86	28.0	.75	.89	8.00		2.99	8.89	.62
FAGU146	8505	23.2	25.2	2.0	100	4A4	3.14	.05	2.90	4.50	43.0	1.03	1.66	6.90		7.40	8.56	.61
FAGU146	8506	25.2	27.9	2.7	100	4A4	3.06	.04	2.70	4.50	39.0	.69	1.47	4.27		7.20	5.74	.63
FAGU146	8507	27.9	29.5	1.6	100	4DL4	3.34	.07	4.40	5.90	69.0	1.10	4.67	8.40		10.30	13.07	.57
FAGU146	8508	29.5	31.2	1.7	94	4A14	3.35	.06	8.10	13.10	143.0	1.10	2.02	5.70		21.20	7.72	.62
FAGU146	8509	31.2	32.4	1.2	75	4L4	3.37	.13	3.40	3.50	54.0	.96	3.30	13.00		6.90	16.30	.51
FAGU146	8510	39.1	41.6	2.5	100	4ADL	3.30	.16	1.72	3.50	37.0	.69	1.64	12.90		5.22	14.54	.67
FAGU146	8511	44.1	46.9	2.8	100	4A0	3.45	.15	1.25	2.30	29.0	1.44	1.38	17.10		3.55	18.48	.65
FAGU146	8512	46.9	47.9	1.0	100	4A0	3.74	.25	1.05	.55	32.0	1.30	1.31	25.80		1.60	27.11	.34
FAGU146	8513	47.9	49.1	1.2	92	4D4	4.25	.20	6.50	9.50	111.0	1.71	1.84	24.60		16.00	26.44	.59
FAGAG81	8514	54.6	56.7	2.1	100	4LC	3.39	.11	1.85	2.60	27.0	.34	5.36	10.50		4.45	15.86	.58
FAGAG81	8515	56.7	57.8	1.1	100	4E*8	3.99	.16	2.70	2.40	42.0	1.03	6.84	26.00		5.10	32.84	.47
FAGAG81	8516	57.8	59.3	1.5	93	4A3	3.56	.20	.19	.30	13.0	.82	2.03	23.20		.49	25.23	.61
FAGAG81	8517	59.3	60.4	1.1	82	5D4*	3.10	.05	.27	.65	8.0	.41	4.00	6.50		.92	10.50	.71
FAGAG81	8518	60.4	61.9	1.5	60	4E15	3.98	.41	.45	.44	18.0	.89	1.17	29.70		.89	30.87	.49

DDH	SAMPLE	---DEPTHS---	INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAO	PB+ZN	PO+PY	ZN
		FROM TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGA081	8519	61.9	63.4	1.5	47	4E15	4.30	.43	5.50	6.60	76.0	1.17	1.21	26.70	12.10	27.91	.55
FAGA081	8520	63.4	64.3	.9	100	4E#G4	4.91	.12	13.60	11.80	179.0	1.17	1.47	24.20	25.40	25.67	.46
FAGA081	8521	64.3	65.7	1.4	36	4L31	3.60	.28	1.72	1.96	31.0	1.51	3.00	18.90	3.68	21.90	.53
FAGA081	8522	65.7	67.1	1.4	64	4L31	3.45	.19	1.08	.87	19.0	.27	2.19	18.50	1.95	20.69	.45
FAGA081	8523	67.1	68.3	1.2	92	4E4	4.69	.18	9.40	10.30	126.0	1.23	3.15	26.60	19.70	29.75	.52
FAGA081	8524	68.3	69.6	1.3	38	4E4	4.78	.19	5.70	7.40	77.0	.48	2.90	32.30	13.10	35.20	.56
FAGA081	8525	69.6	71.1	1.5	67	4E#4	4.69	.01	.15	.19	6.0	1.23	3.62	28.70	.34	32.32	.56
FAGA081	8526	173.2	173.8	.6	83	4E0	4.14	.32	8.80	8.40	122.0	.27	6.40	30.70	17.20	37.10	.49
FAGA081	8527	173.8	174.3	.5	100	4C#7	3.57	.15	1.26	1.63	27.0	.07	4.94	18.40	2.89	23.34	.56
FAGA081	8528	174.3	175.6	1.3	100	4CE8	3.64	.16	1.99	2.40	32.0	.55	6.52	17.90	4.39	24.42	.55
FAGA081	8529	175.6	176.9	1.3	100	4CE8	3.55	.12	1.88	2.10	29.0	.75	5.61	15.90	3.98	21.51	.53
FAGA081	8530	176.9	177.8	.9	100	4L1	3.27	.08	1.17	1.58	21.0	.34	5.01	10.30	2.75	15.31	.57
FAGA081	8531	184.3	185.8	1.5	100	4E*6	3.54	.12	2.06	2.80	32.0	1.03	5.49	15.90	4.86	21.39	.58
FAGAC81	8532	185.8	187.5	1.7	100	4E*1	3.45	.10	2.09	2.30	32.0	.55	6.07	12.40	4.39	18.47	.52
FAGAC81	8533	188.1	190.3	2.2	95	4E*1	3.43	.07	1.85	2.40	25.0	.34	6.38	10.90	4.25	17.28	.56
FAGA081	8534	190.3	192.4	2.1	100	4E*1	3.29	.08	1.67	1.84	23.0	.41	4.14	8.60	3.51	12.74	.52
FAGA081	8535	192.4	193.1	.7	100	4A3	3.45	.12	1.86	2.50	29.0	.41	6.65	12.40	4.36	19.05	.57
FAGU179	8536	.0	2.2	2.2	77	4C3	3.65	.28	1.60	1.67	26.0	.75	3.76	20.10	3.27	23.86	.51
FAGU179	8537	2.2	4.6	2.4	96	4C3	3.74	.43	.28	1.03	16.0	.96	3.79	24.50	1.31	28.29	.79
FAGU179	8538	4.6	5.3	.7	100	5B6	2.95	.03	.24	.51	5.0	.27	3.65	3.08	.75	6.73	.68
FAGU179	8539	5.3	6.3	1.0	100	4C0	3.45	.24	2.00	3.20	39.0	1.44	3.90	17.80	5.20	21.70	.62
FAGU179	8540	6.3	7.9	1.6	88	4EA4	3.65	.13	5.70	6.60	76.0	2.13	2.38	15.60	12.30	17.98	.54
FAGU179	8541	7.9	9.9	2.0	100	4D4	3.79	.19	7.50	11.10	115.0	2.26	2.78	14.90	18.60	17.68	.60
FAGU179	8542	9.9	14.0	4.1	56	4D4	3.71	.07	9.60	21.60	152.0	1.78	3.66	6.20	31.20	9.86	.69
FAGU179	8543	14.0	16.1	2.1	90	4D4	3.93	.06	9.60	22.40	165.0	2.06	2.56	8.40	32.00	10.96	.70
FAGU179	8544	30.2	32.4	2.2	100	4G4	4.33	.05	4.30	9.80	67.0	.89	1.62	15.30	14.10	16.92	.70
FAGU179	8545	32.4	34.6	2.2	100	4G0	4.60	.03	1.02	2.90	19.0	.34	.95	22.40	3.92	23.35	.74
FAGU179	8546	34.6	36.9	2.3	100	4G0	4.69	.02	2.60	6.50	31.0	.55	.74	21.60	9.10	22.34	.71
FAGU179	8547	36.9	39.1	2.2	86	4E4	4.61	.15	3.30	4.60	60.0	.96	1.45	31.80	7.90	33.25	.58
FAGU179	8548	39.1	41.1	2.0	100	4E4	4.67	.17	3.30	3.50	382.0	1.44	1.60	35.40	6.80	37.00	.51
FAGU179	8549	41.1	45.7	4.6	22	4E4	4.21	.20	3.80	3.90	52.0	1.17	1.42	31.30	7.70	32.72	.51
FAGU152	8550	14.1	14.5	.4	75	4D7		.02	1.89	4.50	32.0				6.39		.70
FAGU152	8551	18.6	19.4	.8	62	4A4	3.34	.08	2.05	4.00	32.0	1.03	1.80	14.10	6.05	15.90	.66
FAGU152	8552	19.4	20.9	1.5	80	4C0	3.21	.16	.96	2.40	13.0	.48	1.93	12.20	3.36	14.13	.71
FAGU152	8553	21.3	22.9	1.6	75	4DC	3.04	.06	2.70	2.80	30.0	1.03	.72	6.20	5.50	6.92	.51
FAGU152	8554	22.9	24.4	1.5	80	4D0	3.01	.07	3.20	3.80	39.0	1.10	.94	3.26	7.00	4.20	.54
FAGU152	8555	24.4	26.4	2.0	95	4A0	2.94	.05	.91	1.14	15.0	.48	.78	3.67	2.05	4.45	.56
FAGU152	8556	26.4	28.4	2.0	100	4A0	2.91	.04	.24	.58	4.0	.41	.61	4.88	.82	5.49	.71
FAGU152	8557	28.4	30.3	1.9	100	4A0	2.92	.04	.38	.55	7.0	.41	1.19	3.98	.93	5.17	.59
FAGU152	8558	33.5	34.5	1.0	80	4D4	2.92	.02	3.50	6.80	52.0	.48	3.34	3.09	10.30	6.43	.66
FAGU152	8559	35.0	37.0	2.0	100	4A0	3.16	.03	1.50	2.90	24.0	.75	.88	11.10	4.40	11.98	.66
FAGU152	8560	37.0	39.3	2.3	100	4A4	3.38	.08	2.08	4.70	34.0	.96	.98	16.00	6.78	16.98	.69
FAGU152	8561	39.3	40.9	1.6	100	4AE4	3.86	.22	3.50	7.70	65.0	1.17	2.20	18.90	11.20	21.10	.69
FAGU152	8562	40.9	42.9	2.0	100	4AE4	3.50	.17	1.88	4.30	38.0	1.23	1.29	14.90	6.18	16.19	.70
FAGU152	8563	42.9	45.0	2.1	100	4DE	4.13	.20	3.60	4.50	65.0	1.78	2.86	24.50	8.10	27.36	.56
FAGU152	8564	45.0	46.7	1.7	100	4CA	3.55	.28	.39	.91	20.0	1.10	1.84	20.10	1.30	21.94	.70
FAGU056	8565	.0	3.1	3.1	39	4LA1	2.71	.03	1.40	2.50	26.0	.55	.81	6.10	3.90	6.91	.64
FAGUC56	8566	3.1	6.2	3.1	100	4LA1	2.84	.06	.49	1.87	15.0	.55	1.60	6.10	2.36	7.70	.79
FAGU056	8567	6.2	9.3	3.1	100	4LA1	3.01	.04	1.25	4.00	25.0	.82	1.58	4.92	5.25	6.50	.76
FAGU056	8568	9.3	12.3	3.0	100	4LA1	3.08	.08	1.18	3.20	28.0	.62	1.53	7.20	4.38	8.73	.73

DDH	SAMPLE	---DEPTHS---	INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PC	PY	BAO	PB+ZN	PC+PY	ZN
		FROM TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGU056	8569	12.3 15.3	3.0	100	4LA1	3.14	.02	1.25	3.80	28.0	.55	1.11	9.00		5.05	10.11	.75
FAGU056	8570	15.3 18.3	3.0	100	4LA1	3.14	.03	1.71	3.00	39.0	.69	1.67	9.10		4.71	10.77	.64
FAGU056	8571	18.3 21.3	3.0	70	4LA1	3.50	.05	1.97	3.70	31.0	.69	1.72	3.03		5.67	4.75	.65
FAGU056	8572	21.3 24.3	3.0	43	4A1	3.11	.04	1.09	2.20	23.0	.41	1.82	2.54		3.29	4.36	.67
FAGU056	8573	45.4 47.7	2.3	100	4A3	3.51	.07	1.23	2.30	26.0	.62	1.05	11.50		3.53	12.55	.65
FAGU056	8574	47.7 50.1	2.4	100	4A3	2.92	.05	.72	1.13	16.0	.48	.72	7.40		1.85	8.12	.61
FAGU056	8575	50.1 50.6	.5	100	4CL	2.86	.01	.19	.19	6.0	.21	5.00	1.40		.38	6.40	.50
FAGU056	8576	50.6 51.3	.7	71	5D4	2.84	.03	.14	.11	5.0	.27	4.96	.96		.25	5.92	.44
FAGU056	8577	51.3 52.3	1.0	100	4L14	3.23	.03	2.40	2.10	27.0	.48	1.82	1.67		4.50	3.49	.47
FAGU056	8578	52.3 53.3	1.0	100	4A14	3.06	.04	5.50	6.50	60.0	1.44	1.24	4.70		12.00	5.94	.54
FAGU056	8579	53.3 55.5	2.2	100	4A4	3.01	.04	3.30	6.50	42.0	.69	1.05	5.60		9.80	6.65	.66
FAGU030	8580	3.0 4.6	1.6	94	4EL	3.86	.16	3.70	3.10	72.0	.62	3.30	20.50		6.80	23.80	.46
FAGU030	8581	4.6 6.3	1.7	100	4EL	3.54	.15	.65	.21	25.0	.41	4.53	16.90		.86	21.43	.24
FAGU030	8582	6.3 7.9	1.6	100	4G4	4.30	.16	5.60	4.80	98.0	1.10	2.99	17.10		10.40	20.09	.46
FAGU030	8583	7.9 9.6	1.7	100	4G4	4.39	.11	8.10	7.50	128.0	.48	1.86	7.90		15.60	9.76	.48
FAGU030	8584	9.6 12.3	2.7	100	4LC	3.80	.11	1.19	1.16	21.0	1.92	5.50	10.40		2.35	15.90	.49
FAGU030	8585	12.3 15.0	2.7	100	4LC	3.21	.10	1.08	1.21	18.0	.21	6.30	8.50		2.29	14.80	.53
FAGU030	8586	15.0 17.7	2.7	100	4LC	3.18	.07	1.26	1.37	18.0	.14	4.96	6.60		2.63	11.56	.52
FAGU030	8587	17.7 20.3	2.6	100	4LC	3.14	.11	1.06	1.24	18.0	.27	4.81	5.40		2.30	10.21	.54
FAGU030	8588	20.3 21.4	1.1	91	4LC	3.09	.03	.06	.07	9.0	.21	2.10	2.46		.13	4.56	.54
FAGU030	8589	21.4 23.1	1.7	100	4LC	3.07	.11	.58	.91	16.0	.21	5.30	6.50		1.49	11.80	.61
FAGU030	8590	23.1 24.8	1.7	100	4LC	3.37	.10	1.82	1.82	34.0	.27	4.57	8.70		3.64	13.27	.50
FAGU030	8591	24.8 26.0	1.2	100	4E86	3.98	.30	3.30	2.80	51.0	.55	8.10	20.50		6.10	28.60	.46
FAGU030	8592	26.0 29.0	3.0	97	4EL8	3.70	.23	4.10	3.20	58.0	.41	4.50	17.60		7.30	22.10	.44
FAGA058	8593	133.0 134.9	1.9	84	4G4	4.45	.13	7.60	6.00	95.0	1.44	10.00	14.30		13.60	24.30	.44
FAGA058	8594	134.9 136.7	1.8	100	4G4	4.56	.10	4.80	6.30	75.0	.75	2.58	19.30		11.10	21.88	.57
FAGA058	8595	136.7 137.6	.9	89	4G4	3.40	.04	2.02	4.60	43.0	.34	2.81	9.00		6.62	11.81	.69
FAGA058	8596	138.3 139.5	1.2	92	4G4	4.58	.14	7.10	8.40	123.0	1.17	3.76	18.10		15.50	21.86	.54
FAGA058	8597	139.5 140.8	1.3	100	4G4	4.49	.03	6.20	8.00	87.0	.62	1.67	13.60		14.20	15.27	.56
FAGA058	8598	140.8 142.2	1.4	100	4C3	4.78	.24	.93	1.65	26.0	1.51	5.72	28.90		2.58	34.62	.64
FAGA058	8599	142.2 143.4	1.2	100	4D84	2.88	.15	6.20	4.30	75.0	.62	6.52	18.30		10.50	24.82	.41
FAGA058	8600	143.4 145.4	2.0	100	4C3	3.76	.19	.95	.66	27.0	2.13	2.76	24.40		1.61	27.16	.41
FAGA027	8601	184.5 185.6	1.1	100	4C0		.08	1.07	1.48	23.0					2.55		.58
FAGA027	8602	185.6 186.2	.6	83	4A0	2.89	.05	.11	.11	6.0	.48	.89	6.80		.22	7.69	.50
FAGA027	8603	186.2 188.0	1.8	83	4C0	3.10	.12	.54	.86	14.0	.62	2.26	11.10		1.40	13.36	.61
FAGA027	8604	188.0 189.1	1.1	100	4C0	2.91	.04	.38	.67	8.0	.21	2.85	4.46		1.05	7.31	.64
FAGA027	8605	189.1 190.8	1.7	100	4A0	2.89	.05	.65	1.06	15.0	.41	.87	6.08		1.71	6.95	.62
FAGA027	8606	190.8 192.3	1.5	100	4C0	2.95	.04	.56	1.14	12.0	.48	1.14	4.16		1.70	5.30	.67
FAGA027	8607	192.3 193.9	1.6	94	4C0	3.06	.09	.78	2.40	14.0	.55	1.30	7.30		3.18	8.60	.75
FAGA027	8608	193.9 195.2	1.3	100	4C0	3.00	.06	.54	1.51	11.0	.55	1.01	5.20		2.05	6.21	.74
FAGA027	8609	195.2 196.9	1.7	94	4A1	3.23	.16	1.09	1.98	23.0	.82	1.06	13.00		3.07	14.06	.64
FAGA027	8610	196.9 199.2	2.3	78	4A1	3.31	.09	1.73	2.60	34.0	1.03	1.80	13.80		4.33	15.60	.60
FAGA027	8611	199.2 200.6	1.4	100	4A14	3.38	.03	3.90	10.00	63.0	.69	2.04	9.50		13.90	11.54	.72
FAGA027	8612	200.6 202.2	1.6	94	4A14	3.03	.06	1.70	3.80	32.0	.48	2.52	3.91		5.50	6.43	.69
FAGA027	8613	202.2 203.7	1.5	100	4A1	2.87	.01	1.03	2.30	19.0	.27	1.41	.72		3.33	2.13	.69
FAGA027	8614	203.7 205.4	1.7	100	5B629	2.90	.01	.45	1.26	7.0	.27	1.15	.93		1.71	2.08	.74
FAGA027	8615	205.4 206.9	1.5	87	5B629	3.13	.01	1.30	3.60	25.0	.55	2.71	5.40		4.90	8.11	.73
FAGA027	8616	206.9 208.4	1.5	87	4A14	3.48	.02	2.03	5.10	39.0	.82	2.97	15.20		7.13	18.17	.72
FAGA027	8617	208.4 209.9	1.5	93	4A1	3.00	.01	.26	.65	5.0	.41	2.24	2.15		.91	4.39	.71
FAGA027	8618	259.7 261.2	1.5	100	4A0	3.13	.15	.37	.77	14.0	3.43	1.12	10.70		1.14	11.82	.68

DDH	SAMPLE	---DEPTHS---	INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAO	PB+ZN	PC+PY	ZN	
		FROM	TO	M	%	UNIT	%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO	
FAGA027	8619	261.2	262.7	1.5	93	4A0	3.14	.37	1.50	2.50	36.0	1.03	1.30	10.40		4.00	11.70	.63
FAGA027	8620	262.7	264.3	1.6	94	4A4	3.16	.10	2.80	2.40	38.0	1.17	1.16	8.90		5.20	10.06	.46
FAGA027	8621	264.3	265.8	1.5	100	4A4	3.06	.09	3.10	2.30	39.0	.14	.65	8.00		5.40	8.65	.43
FAGA027	8622	265.8	267.3	1.5	60	4A4	3.06	.07	3.40	3.30	43.0	.21	.78	6.30		6.70	7.08	.49
FAGA027	8623	267.3	268.8	1.5	80	4A0	3.46	.13	.59	.90	18.0	1.03	1.04	19.50		1.49	20.54	.60
FAGA027	8624	268.8	270.4	1.6	94	4A0	3.28	.08	2.12	2.60	41.0	1.03	1.07	12.90		4.72	13.97	.55
FAGA027	8625	270.4	271.9	1.5	93	4A4	3.19	.06	3.20	2.90	40.0	1.10	.75	9.20		6.10	9.95	.48
FAGA027	8626	271.9	273.4	1.5	87	4A4	3.06	.05	3.30	3.00	41.0	.89	.72	5.80		6.30	6.52	.48
FAGA027	8627	273.4	274.9	1.5	100	4A0	3.12	.07	.97	1.19	19.0	.96	.83	9.90		2.16	10.73	.55
FAGA027	8628	277.3	278.9	1.6	100	4A1	3.08	.06	.89	.83	15.0	.89	.74	9.20		1.72	9.94	.48
FAGA027	8629	278.9	280.4	1.5	100	4A14	3.06	.05	2.11	3.60	34.0	.89	.81	6.00		5.71	6.81	.63
FAGA027	8630	280.4	281.9	1.5	100	4A14	3.13	.04	3.00	4.10	40.0	.75	.94	6.20		7.10	7.14	.58
FAGAG27	8631	281.9	283.5	1.6	94	4A1	3.20	.09	.69	1.07	14.0	.75	.92	13.40		1.76	14.32	.61
FAGAG27	8632	283.5	285.0	1.5	93	4A13	3.31	.11	.38	.86	12.0	.89	1.69	16.20		1.24	17.89	.69
FAGA027	8633	285.0	287.1	2.1	100	4A13	3.41	.12	.17	.41	8.0	.75	1.25	18.60		.58	19.85	.71
FAGA027	8634	287.1	287.5	.4	100	4G4	4.37	.10	4.90	8.00	100.0	1.10	1.02	20.00		12.90	21.02	.62
FAGAG27	8635	326.3	327.4	1.1	91	4G4	4.86	.08	4.10	7.00	64.0	.89	.90	24.90		11.10	25.80	.63
FAGA027	8636	327.4	327.7	.3	100	5C1	3.05	.01	.19	.45	6.0	.89	2.43	2.18		.64	4.61	.70
FAGA027	8637	327.7	328.9	1.2	100	4E0	4.84	.07	1.99	2.30	43.0	.89	1.33	32.90		4.29	34.23	.54
FAGAG27	8638	328.9	330.2	1.3	92	4E0	4.72	.08	2.06	2.90	44.0	.62	1.45	33.40		4.96	34.85	.58
FAGA027	8639	330.2	331.2	1.0	100	4L1	3.20	.01	.03	.05	3.0	.21	1.29	4.17		.08	5.46	.63
FAGAG27	8640	331.2	332.0	.8	100	5C4*	3.50	.01	1.35	1.40	23.0	.27	2.66	13.00		2.75	15.66	.51
FAGA027	8641	332.0	333.8	1.8	89	4G0	4.81	.04	2.60	5.10	49.0	.69	.70	18.60		7.70	19.30	.66
FAGA027	8642	333.8	335.6	1.8	94	4G4	4.40	.07	4.70	10.00	94.0	.96	1.01	15.40		14.70	16.41	.68
FAGA027	8643	335.6	337.0	1.4	100	4E41	4.54	.17	5.50	8.10	82.0	1.58	1.50	25.90		13.60	27.40	.60
FAGA027	8644	337.0	338.5	1.5	100	4E41	4.54	.31	3.20	4.90	51.0	1.71	1.17	30.50		8.10	31.67	.60
FAGAG27	8645	338.5	340.0	1.5	100	4E41	4.51	.43	2.07	3.90	37.0	1.92	1.41	33.70		5.97	35.11	.65
FAGAG27	8646	340.0	341.2	1.2	100	4D0	4.18	.26	2.80	3.40	49.0	2.81	2.53	26.80		6.20	29.33	.55
FAGA027	8647	341.2	342.5	1.3	85	4D0	3.71	.23	2.70	5.50	50.0	1.17	2.60	17.50		8.20	20.10	.67
FAGAG27	8648	342.5	344.7	2.2	95	4D43	3.78	.12	6.20	9.80	102.0	1.44	3.34	12.20		16.00	15.54	.61
FAGA027	8649	258.2	259.7	1.5	93	4L124	3.10	.17	.47	.78	12.0	.75	1.07	8.40		1.25	9.47	.62
FAGA027	8650	344.7	345.6	.9	100	4D4	3.72	.17	4.70	7.90	70.0	2.74	2.19	14.70		12.60	16.89	.63
FAGA026	8651	113.5	115.1	1.6	100	4A13		.29	.46	1.31	19.0					1.77		.74
FAGA026	8652	115.1	116.6	1.5	100	4A13		.26	.13	.79	10.0					.92		.86
FAGAG26	8653	116.6	118.1	1.5	100	4A13		.15	.21	1.28	13.0					1.49		.86
FAGA026	8654	118.1	119.6	1.5	100	4A13		.23	.04	.59	7.0					.63		.94
FAGA026	8655	119.6	121.2	1.6	100	4A13		.22	.08	.52	5.0					.60		.87
FAGA026	8656	121.2	122.7	1.5	100	4A13		.28	.06	.79	11.0					.85		.93
FAGA026	8657	122.7	124.2	1.5	100	4A13		.16	.02	1.71	2.0					1.73		.99
FAGAG26	8658	124.2	125.7	1.5	100	4A13		.24	.03	1.28	5.0					1.31		.98
FAGA026	8659	125.7	127.3	1.6	100	4A13		.04	.02	1.15	1.0					1.17		.98
FAGA026	8660	127.3	128.5	1.2	100	4A13		.16	.02	.94	2.0					.96		.98
FAGA026	8661	181.5	182.5	1.0	100	4H3	4.29	.24	3.40	3.60	68.0	.01	14.10	25.00		7.00	39.10	.51
FAGA026	8662	182.5	183.3	.8	100	4D7	3.53	.26	1.64	2.20	19.0	.21	23.60	2.20		3.84	25.80	.57
FAGA026	8663	209.5	210.4	.9	100	4L0	2.95	.05	.37	.69	8.0	.48	1.73	4.24		1.06	5.97	.65
FAGAG28	8664	85.1	85.6	.5	100	4A3	3.25	.02	.70	1.00	15.0	.27	3.38	8.90		1.70	12.28	.59
FAGAG28	8665	85.6	86.9	1.3	100	4G4	4.70	.18	6.30	11.20	109.0	.89	1.95	19.20		17.50	21.15	.64
FAGAG28	8666	86.9	88.2	1.3	100	4G4	4.88	.23	6.10	9.20	121.0	.96	1.83	21.30		15.30	23.13	.60
FAGAG28	8667	88.2	89.4	1.2	100	5C4*	3.21	.04	1.18	.87	19.0	.34	3.47	8.50		2.05	11.97	.42
FAGAG28	8668	89.4	90.1	.7	100	4G4	4.66	.22	5.90	8.50	115.0	1.58	1.29	19.00		14.40	20.29	.59

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAO	PB+ZN	PC+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGA028	8669	91.8	92.7	.9	100	4EG4#	4.30	.05	6.10	10.00	110.0	.41	4.14	13.60		16.10	17.74	.62
FAGA028	867C	114.1	116.7	2.6	35	4A1	2.91	.03	.73	1.40	12.0	.21	2.48	1.07		2.13	3.55	.66
FAGA028	8671	116.7	118.6	1.9	53	4A1	2.86	.06	.70	1.49	13.0	.21	2.33	3.87		2.19	6.20	.68
FAGA028	8672	123.1	124.3	1.2	92	4A1		.06	.27	.47	7.0					.74		.64
FAGA028	8673	124.3	125.1	.8	100	4E7	3.25	.05	.97	1.64	17.0	.07	9.10	10.90		2.61	20.00	.63
FAGA028	8674	125.1	126.5	1.4	86	4H3	3.58	.08	.90	1.40	20.0	.01	11.20	15.60		2.30	26.80	.61
FAGA028	8675	126.5	128.0	1.5	80	4H3		.12	.65	.97	19.0					1.62		.60
FAGA028	8676	128.0	129.5	1.5	100	4A3		.12	.33	.56	7.0					.89		.63
FAGA028	8677	129.5	131.1	1.6	69	4A3		.13	.57	.78	11.0					1.35		.58
FAGA028	8678	131.1	132.7	1.6	69	4A3		.26	.22	.28	20.0					.50		.56
FAGA028	8679	132.7	133.9	1.2	50	4C*8		.19	.73	1.02	24.0					1.75		.58
FAGA028	868C	193.6	195.6	2.0	100	4LC7		.09	.35	.55	12.0					.90		.61
FAGA028	8681	213.3	214.9	1.6	56	4E8#	3.71	.14	.77	1.00	23.0	.41	3.23	22.40		1.77	25.63	.56
FAGA028	8682	214.9	216.4	1.5	93	4E8#	3.89	.26	1.97	1.73	32.0	.69	7.60	20.40		3.70	28.00	.47
FAGA028	8683	216.4	217.9	1.5	87	4E8#	3.75	.36	1.94	1.79	39.0	1.78	5.44	17.20		3.73	22.64	.48
FAGA028	8684	217.9	219.5	1.6	94	4E8#	3.80	.16	1.76	1.75	34.0	.55	7.00	20.10		3.51	27.10	.50
FAGA028	8685	219.5	221.0	1.5	87	4E8#	4.39	.17	4.70	3.80	62.0	.96	8.98	24.40		8.50	33.38	.45
FAGA028	8686	221.0	222.5	1.5	80	4E8#	3.73	.25	1.29	.78	22.0	1.37	6.90	18.20		2.07	25.10	.38
FAGA028	8687	222.5	224.0	1.5	53	4E8#	3.98	.23	.77	.40	20.0	1.78	7.50	24.00		1.17	31.50	.34
FAGA028	8688	224.0	225.6	1.6	75	4E8#	4.02	.19	2.00	1.03	34.0	.48	7.80	24.10		3.03	31.90	.34
FAGA028	8689	225.6	227.1	1.5	87	4E8#	4.35	.29	3.40	2.03	45.0	1.71	1.06	33.70		5.43	34.76	.37
FAGA028	869C	227.1	228.2	1.1	100	4E8#	3.67	.18	2.70	3.70	37.0	1.30	2.62	20.20		6.40	22.82	.58
FAGA028	8691	252.7	253.2	.5	100	4C0		.26	1.18	1.26	19.0					2.44		.52
FAGA028	8692	253.2	255.7	2.5	92	4A3		.19	.94	.90	15.0					1.84		.49
FAGA028	8693	260.3	261.8	1.5	100	4A3		.17	.94	.79	18.0					1.73		.46
FAGU048	8694	.0	1.0	1.0	100	4A4	3.59	.03	3.00	8.90	63.0	.96	1.58	16.70		11.90	18.28	.75
FAGU048	8695	1.0	3.3	2.3	100	4E0	3.95	.04	7.90	7.50	120.0	1.10	1.58	19.30		15.40	20.88	.49
FAGU048	8696	3.3	4.2	.9	67	4E41	4.38	.10	7.80	3.90	90.0	1.51	2.02	27.30		11.70	29.32	.33
FAGU048	8697	4.2	6.4	2.2	100	4D0	3.75	.09	4.40	3.70	53.0	1.17	2.26	19.90		8.10	22.16	.46
FAGU048	8698	6.4	8.3	1.9	100	4D0	3.23	.05	2.50	4.90	40.0	.96	1.84	8.50		7.40	10.34	.66
FAGU048	8699	8.3	10.5	2.2	95	4A1	2.87	.03	1.33	2.90	20.0	.75	.99	.65		4.23	1.64	.69
FAGU048	8700	10.5	12.5	2.0	100	4A1	3.09	.06	2.10	3.20	40.0	.75	1.16	5.50		5.30	6.66	.60
FAGA035	8701	160.3	161.8	1.5	100	4E0	4.64	.12	.98	.26	35.0	1.23	2.38	35.60		1.24	37.98	.21
FAGA035	8702	161.8	163.3	1.5	80	4E4	4.63	.22	4.20	4.00	72.0	1.51	1.86	32.50		8.20	34.36	.49
FAGA035	8703	164.0	166.0	2.0	100	4G0	4.42	.14	4.20	4.00	63.0	1.03	3.62	22.20		8.20	25.82	.49
FAGA035	8704	167.2	168.4	1.2	100	4G0	4.31	.13	3.90	4.30	58.0	.96	2.38	23.10		8.20	25.48	.52
FAGA035	8705	168.4	169.6	1.2	100	4L14	3.45	.11	1.31	1.78	21.0	.48	5.18	13.80		3.09	18.98	.58
FAGA035	8706	169.6	171.4	1.8	94	4D64	4.17	.13	5.20	5.20	72.0	.82	4.99	21.30		10.40	26.29	.50
FAGA035	8707	171.4	172.5	1.1	82	4L4	4.17	.17	.88	1.03	14.0	.27	2.07	9.00		1.91	11.07	.54
FAGA035	8708	285.6	286.1	.5	80	4L4	3.18	.10	1.21	1.77	19.0	.27	4.45	9.60		2.98	14.05	.59
FAGA035	8709	286.1	288.1	2.0	80	4A30	3.27	.18	.36	.34	9.0	.62	2.08	14.40		.70	16.48	.49
FAGA035	8710	288.1	290.2	2.1	71	4A30	3.77	.14	1.05	.78	20.0	.75	3.47	16.50		1.83	19.97	.43
FAGA035	8711	330.4	331.1	.7	100	4C8		.19	1.76	1.88	31.0					3.64		.52
FAGA035	8712	331.1	331.9	.8	75	4E88		.23	.61	.52	17.0					1.13		.46
FAGA035	8713	331.9	333.8	1.9	100	4A0	3.56	.14	.26	.52	9.0	.48	2.14	11.80		.78	13.94	.67
FAGA035	8714	333.8	335.6	1.8	100	4A0	2.98	.09	.99	.68	8.0	.55	2.58	4.98		1.67	7.56	.41
FAGA035	8715	335.6	337.4	1.8	100	4A0	3.22	.15	.51	.37	9.0	.62	2.91	8.00		.88	10.91	.42
FAGA035	8716	337.4	338.8	1.4	79	4A0	3.22	.16	1.22	2.10	20.0	.89	2.80	10.40		3.32	13.20	.63
FAGA035	8717	338.8	339.5	.7	100	4D0	4.08	.29	2.90	3.30	43.0	.89	2.36	26.40		6.20	28.76	.53
FAGA035	8718	339.5	341.1	1.6	100	4A10	2.96	.09	1.20	1.90	20.0	.55	2.16	2.57		3.10	4.73	.61

DDH	SAMPLE	---DEPTHS---	INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAO	PB+ZN	PG+PY	ZN
		FROM TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGA035	8719	341.1	342.7	1.6	81	4A10	3.08	.07	.47	1.16	10.0	.21	3.90	5.80			.71
FAGA035	8720	343.3	344.1	.8	100	4A0	3.44	.05	.90	1.73	18.0	.69	1.81	17.50	1.63	9.70	.66
FAGA035	8721	344.1	345.5	1.4	93	4DL	3.18	.11	3.70	3.70	47.0	.55	1.60	25.50	7.40	27.10	.50
FAGA035	8722	345.5	346.8	1.3	100	4DA	3.86	.15	3.20	3.70	45.0	.82	2.10	22.70	6.90	24.80	.54
FAGA035	8723	346.8	348.7	1.9	95	4A10	3.10	.14	1.13	1.59	20.0	.89	1.94	8.60	2.72	10.54	.58
FAGA035	8724	348.7	350.5	1.8	94	4A10	3.02	.10	.49	.54	9.0	.69	2.96	8.20	1.03	11.16	.53
FAGA035	8725	350.5	352.3	1.8	100	4A10	3.12	.27	.16	.54	8.0	.69	3.38	11.90	.70	15.28	.77
FAGA035	8726	352.3	354.2	1.9	95	4A10	3.12	.14	.13	.78	8.0	.55	1.46	12.30	.91	13.76	.86
FAGA035	8727	354.2	356.3	2.1	100	4A10	3.30	.14	.15	.24	5.0	.41	2.16	9.00	.39	11.16	.62
FAGA035	8728	356.3	357.5	1.2	75	4D8S	4.54	.10	3.60	4.00	54.0	.96	4.77	26.90	7.60	31.67	.53
FAGA035	8729	357.5	359.4	1.9	100	4A10		.20	.21	.71	11.0				.92		.77
FAGA035	8730	359.4	361.4	2.0	95	4A10		.10	.16	.28	8.0				.44		.64
FAGA035	8731	364.8	367.0	2.2	95	4H2	4.31	.19	1.72	2.07	37.0	.34	12.99	23.20	3.79	36.19	.55
FAGA035	8732	367.0	368.3	1.3	69	4H2	3.78	.32	.99	1.02	29.0	.21	19.38	12.80	2.01	32.18	.51
FAGUG51	8733	.0	2.5	2.5	88	4A4	3.33	.04	2.90	7.80	54.0	.75	2.85	11.20	10.70	14.05	.73
FAGUG51	8734	2.5	5.0	2.5	100	4A4	3.41	.03	3.10	6.40	60.0	.96	1.81	15.50	9.50	17.31	.67
FAGUG51	8735	5.0	7.6	2.6	92	4A4	3.46	.04	2.20	5.00	44.0	.82	1.43	15.40	7.20	16.83	.69
FAGUG51	8736	7.6	10.1	2.5	64	4C5	2.92	.04	1.82	3.90	33.0	.62	1.90	3.98	5.72	5.88	.68
FAGUG51	8737	10.1	12.6	2.5	64	4C5	3.01	.05	1.60	2.70	29.0	.96	1.34	7.30	4.30	8.64	.63
FAGUG51	8738	12.6	15.2	2.6	42	4C5	2.96	.03	2.60	2.60	41.0	.96	1.72	4.44	5.20	6.16	.50
FAGUG51	8739	22.9	24.0	1.1	82	4A4	3.10	.03	3.50	5.70	71.0	.96	2.68	6.50	9.20	9.18	.62
FAGUG51	8740	24.0	27.4	3.4	88	5D4	3.05	.04	1.20	4.70	23.0	.48	6.30	3.97	5.90	10.27	.80
FAGUG51	8741	27.4	29.2	1.8	67	4A41	3.42	.03	1.78	4.30	30.0	.96	1.31	2.82	6.08	4.13	.71
FAGUG51	8742	29.2	29.9	.7	86	4L14	2.85	.03	1.34	4.20	25.0	1.85	1.29	2.37	5.54	3.66	.76
FAGUG51	8743	29.9	30.7	.8	100	5C4*	2.85	.01	.06	.12	2.0	.27	5.55	1.54	.18	7.09	.67
FAGUG51	8744	30.7	31.9	1.2	92	4L124	2.90	.05	1.09	1.84	18.0	.62	.96	5.30	2.93	6.26	.63
FAGUG51	8745	31.9	33.8	1.9	100	4L14	2.84	.05	.93	1.72	15.0	.69	.86	4.12	2.65	4.98	.65
FAGUG51	8746	33.8	35.7	1.9	100	4L14	2.88	.05	.74	1.18	15.0	.69	.76	6.60	1.92	7.36	.61
FAGUG51	8747	35.7	38.2	2.5	96	4A4	3.02	.08	2.50	4.70	45.0	.82	.95	7.20	7.20	8.15	.65
FAGUG51	8748	38.2	40.7	2.5	92	4A4	3.14	.05	1.71	3.10	33.0	.96	1.10	8.90	4.81	10.00	.64
FAGUG51	8749	40.7	41.7	1.0	80	4E4	4.04	.09	8.70	16.30	158.0	1.44	2.58	14.60	25.00	17.18	.65
FAGUG51	8750	.0	2.4	2.4	38	4A14	3.38	.03	1.91	4.10	47.0	.75	1.05	16.60	6.01	17.65	.68
FAGUG51	8751	2.4	4.8	2.4	83	4A14	3.66	.02	1.24	3.90	35.0	.89	1.10	24.20	5.14	25.30	.76
FAGUG51	8752	4.8	7.2	2.4	100	4A14	3.25	.03	1.30	3.70	33.0	.82	.91	14.40	5.00	15.31	.74
FAGUG51	8753	7.2	9.6	2.4	96	4A14	3.33	.04	2.40	6.20	46.0	.89	1.25	14.40	8.60	15.65	.72
FAGUG51	8754	15.7	17.4	1.7	76	4ECO	3.52	.06	1.36	3.00	35.0	1.58	2.26	17.60	4.36	19.86	.69
FAGUG51	8755	17.4	18.1	.7	100	4A4	3.08	.01	4.40	7.30	75.0	.89	1.10	6.30	11.70	7.40	.62
FAGUG51	8756	18.1	18.6	.5	100	4D4	3.15	.01	4.30	7.20	71.0	.75	1.18	7.20	11.50	8.38	.63
FAGUG51	8757	18.6	19.2	.6	100	5D4	2.95	.07	.52	1.20	10.0	.27	3.86	2.67	1.72	6.53	.70
FAGUG51	8758	19.2	19.8	.6	100	4A4	4.12	.01	6.80	6.90	101.0	1.58	1.60	13.40	13.70	15.00	.50
FAGUG51	8759	19.8	20.4	.6	100	5D4	2.87	.04	.13	.13	5.0	.21	4.10	1.50	.26	5.60	.50
FAGUG51	8760	20.4	21.8	1.4	93	4D45	3.37	.02	6.00	11.10	100.0	.75	2.92	8.70	17.10	11.62	.65
FAGUG51	8761	21.8	22.9	1.1	100	5D4	2.88	.02	.18	.21	8.0	.27	5.00	1.91	.39	6.91	.54
FAGUG51	8762	22.9	23.4	.5	100	4DE	3.49	.06	3.70	9.70	66.0	.89	1.58	13.70	13.40	15.28	.72
FAGUG51	8763	22.6	25.4	2.8	100	4D3		.21	1.66	1.81	36.0				3.47		.52
FAGUG51	8764	55.7	56.4	.7	86	4E4	3.96	.17	4.80	8.10	76.0	.34	1.99	24.40	12.90	26.39	.63
FAGUG51	8765	56.4	57.7	1.3	46	4A0	2.91	.02	.57	1.56	13.0	.41	1.34	6.40	2.13	7.74	.73
FAGUG51	8766	57.7	59.8	2.1	95	4E4	3.85	.09	7.40	14.80	117.0	.69	.93	23.60	22.20	24.53	.67
FAGUG51	8767	59.8	62.0	2.2	91	4A4	3.25	.06	3.80	9.50	65.0	1.03	.96	10.50	13.30	11.46	.71
FAGUG51	8768	62.0	64.2	2.2	91	4A0	3.16	.05	1.62	2.50	37.0	.89	.71	12.90	4.12	13.61	.61

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAO	PB+ZN	PC+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGUG29	8769	64.2	66.4	2.2	100	4A0	2.87	.02	1.26	3.60	26.0	.48	.76	2.54		4.86	3.30	.74
FAGUG29	8770	66.4	68.6	2.2	100	4A0	2.81	.01	1.34	3.50	26.0	.41	.81	2.42		4.84	3.23	.72
FAGU032	8771	.0	1.8	1.8	61	4DA	3.47	.03	2.90	4.60	40.0	.96	3.49	14.90		7.50	18.39	.61
FAGU032	8772	27.7	29.4	1.7	82	4LC	2.99	.07	.43	.46	10.0	.27	3.76	6.03		.89	9.79	.52
FAGU032	8773	29.4	30.5	1.1	100	4E48	3.08	.21	2.90	2.40	44.0	.96	7.92	20.80		5.30	28.72	.45
FAGU032	8774	53.3	54.7	1.4	64	4GE	4.57	.22	5.00	8.50	105.0	.89	.67	29.50		13.50	30.17	.63
FAGU032	8775	90.3	92.2	1.9	100	4E4	3.27	.26	3.50	4.20	51.0	.62	1.90	29.40		7.70	31.30	.55
FAGU032	8776	92.2	93.0	.8	100	4CA	3.55	.12	.33	.41	13.0	.34	3.80	13.40		.74	17.20	.55
FAGU032	8777	107.9	111.4	3.5	31	4L2		.12	1.00	.87	22.0						1.87	.47
FAGU032	8778	111.4	112.9	1.5	93	4A3		.08	.57	1.37	13.0						1.94	.71
FAGUC32	8779	118.4	119.2	.8	87	4A1		.05	.68	1.21	14.0						1.89	.64
FAGUG33	8780	2.7	4.9	2.2	91	4ELG	3.16	.16	2.60	2.05	41.0	.69	3.62	12.90		4.65	16.52	.44
FAGU033	8781	6.2	7.0	.8	100	4E7#	4.34	.25	5.70	6.70	88.0	.34	12.40	14.20		12.40	26.60	.54
FAGU033	8782	7.0	7.8	.8	100	4GE4	2.96	.07	7.00	10.20	107.0	.82	2.31	18.00		17.20	20.31	.59
FAGA026	8783	74.5	75.6	1.1	100	4L0	3.17	.01	.74	1.18	15.0	.27	1.36	10.10		1.92	11.46	.61
FAGAG26	8784	75.6	77.4	1.8	67	4L4	3.57	.05	3.80	8.70	70.0	.75	1.56	15.30		12.50	16.86	.70
FAGA026	8785	77.4	79.0	1.6	100	4D4	3.74	.08	6.20	15.90	103.0	1.44	1.82	15.50		22.10	17.32	.72
FAGAG26	8786	79.0	80.7	1.7	76	4D4	4.04	.22	6.00	11.70	110.0	1.71	2.07	20.10		17.70	22.17	.66
FAGAG26	8787	80.7	81.6	.9	100	4D4	3.89	.14	7.80	13.50	133.0	1.78	2.64	18.80		21.30	21.44	.63
FAGA026	8788	81.6	83.0	1.4	57	4E64	4.63	.16	8.70	20.30	158.0	2.33	5.65	19.10		29.00	24.75	.70
FAGAG26	8789	83.0	84.3	1.3	92	4E64	4.37	.02	8.00	16.10	123.0	1.37	2.55	23.00		24.10	25.55	.67
FAGAC26	8790	84.3	85.6	1.3	100	4EA4	3.80	.22	9.10	13.40	146.0	2.47	2.35	15.50		22.50	17.85	.60
FAGAG26	8791	85.6	86.9	1.3	85	4EA4	4.02	.15	10.20	17.60	172.0	3.09	2.23	15.10		27.80	17.33	.63
FAGA026	8792	86.9	88.1	1.2	100	4EA4	3.89	.12	8.90	17.10	159.0	2.33	2.58	15.40		26.00	17.98	.66
FAGA026	8793	88.1	89.6	1.5	100	4EA4	3.75	.20	4.70	5.10	94.0	2.26	1.32	20.80		9.80	22.12	.52
FAGA026	8794	89.6	91.1	1.5	100	4AD4	3.34	.07	6.10	7.80	102.0	1.65	1.41	12.20		13.90	13.61	.56
FAGA026	8795	91.1	92.7	1.6	100	4AD4	3.64	.17	8.10	10.00	127.0	1.71	1.76	12.20		18.10	13.96	.55
FAGA026	8796	92.7	94.2	1.5	100	4AD4	3.44	.08	5.00	7.30	77.0	1.65	1.56	11.20		12.30	12.76	.59
FAGAG26	8797	94.2	96.5	2.3	96	4AD4	3.45	.10	6.00	6.60	80.0	1.71	1.65	15.90		12.60	17.55	.52
FAGA026	8798	109.0	110.5	1.5	100	4A13	3.31	.13	2.40	1.30	40.0	.82	1.90	15.80		3.70	17.70	.35
FAGA026	8799	110.5	112.0	1.5	100	4A13		.16	.78	1.02	23.0						1.80	.57
FAGA026	8800	112.0	113.5	1.5	100	4A13		.36	.15	1.54	133.0						1.69	.91
FAGUC42	8801	.0	2.7	2.7	56	5C4	2.94	.03	.59	.66	12.0	.27	5.20	3.82		1.25	9.02	.53
FAGUG42	8802	2.7	4.8	2.1	100	4CL	3.00	.03	1.11	2.08	21.0	.55	2.70	4.29		3.19	6.99	.65
FAGUG42	8803	4.8	7.3	2.5	100	5C4	3.23	.03	.52	.55	11.0	.34	3.58	4.22		1.07	7.80	.51
FAGUG42	8804	7.3	9.8	2.5	100	4A4	2.99	.05	4.80	5.10	64.0	1.37	.92	6.30		9.90	7.22	.52
FAGUG42	8805	9.8	12.3	2.5	100	4A4	3.20	.03	3.40	7.10	55.0	1.10	1.00	9.90		10.50	10.90	.68
FAGUG42	8806	12.3	14.9	2.6	100	4A4	3.21	.06	5.00	7.60	76.0	1.17	1.15	7.00		12.60	8.15	.60
FAGUG42	8807	14.9	17.1	2.2	91	4CL	2.89	.03	1.00	2.20	19.0	.34	1.48	4.06		3.20	5.54	.69
FAGUG42	8808	17.1	19.7	2.6	100	4A34	3.01	.03	2.40	5.10	37.0	.62	.91	6.30		7.50	7.21	.68
FAGUC42	8809	19.7	22.0	2.3	100	4CL	2.94	.07	1.00	1.74	18.0	.55	.57	6.80		2.74	7.37	.64
FAGUG42	8810	22.0	24.3	2.3	100	4CL	2.92	.05	1.80	3.70	29.0	.41	.86	3.42		5.50	4.28	.67
FAGUG42	8811	24.3	26.5	2.2	100	4CL	2.96	.06	1.09	1.83	19.0	.55	.53	7.70		2.92	8.23	.63
FAGUG42	8812	26.5	29.6	3.1	100	4A4	3.16	.05	2.30	3.50	41.0	.89	.72	12.10		5.80	12.82	.60
FAGUG42	8813	29.6	30.2	.6	100	4E4	3.73	.02	7.00	14.40	118.0	1.03	1.24	15.30		21.40	16.54	.67
FAGUG42	8814	30.2	32.9	2.7	100	4E4	4.39	.06	5.50	11.90	97.0	.41	.74	29.20		17.40	29.94	.68
FAGUG42	8815	32.9	33.8	.9	100	4J4	3.68	.09	9.00	17.70	164.0	1.44	2.17	4.54		26.70	6.71	.66
FAGUG49	8816	.0	2.8	2.8	100	4C5	2.84	.03	1.42	3.20	24.0	.62	.76	4.23		4.62	4.99	.69
FAGUG49	8817	2.8	5.6	2.8	89	4D5	2.96	.03	1.64	3.70	29.0	.69	.91	5.50		5.34	6.41	.69
FAGUG49	8818	5.6	8.4	2.8	100	4D5	3.06	.08	2.10	3.90	38.0	.89	1.24	7.70		6.00	8.94	.65

DDH	SAMPLE	----DEPTHS----		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAC	PB+ZN	PC+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGU049	8819	8.4	11.2	2.8	100	4C5	2.89	.02	.96	3.70	16.0	.48	1.67	3.32		4.66	4.99	.79
FAGU049	8820	11.2	14.1	2.9	100	4C5	2.91	.06	1.54	3.20	25.0	.48	1.10	3.88		4.74	4.98	.68
FAGU049	8821	14.1	16.5	2.4	100	4L14	3.00	.10	2.20	3.60	38.0	.75	1.19	4.71		5.80	5.90	.62
FAGU049	8822	16.5	18.9	2.4	100	4L14	2.95	.09	2.40	5.00	42.0	.62	1.31	3.07		7.40	4.38	.68
FAGU049	8823	18.9	21.3	2.4	88	4L14	3.00	.07	2.40	7.30	49.0	.62	1.52	2.56		9.70	4.08	.75
FAGU049	8824	76.2	79.2	3.0	100	4C5	2.84	.04	1.29	2.20	20.0	.48	1.58	2.16		3.49	3.74	.63
FAGU049	8825	79.2	82.3	3.1	100	4C5	2.91	.05	1.34	.35	10.0	.75	.56	3.44		1.69	4.00	.21
FAGA105	8826	130.1	131.6	1.5	100	4CA		.29	.18	.46	12.0					.64		.72
FAGA105	8827	131.6	133.7	2.1	95	4A13		.19	.21	.39	10.0					.60		.65
FAGA105	8828	133.7	135.8	2.1	100	4A13		.14	.85	1.25	13.0					2.10		.60
FAGA105	8829	135.8	137.9	2.1	100	4A13		.19	.17	.27	7.0					.44		.61
FAGA105	8830	137.9	139.9	2.0	100	4A13		.24	.17	.21	7.0					.38		.55
FAGA105	8831	139.9	141.9	2.0	100	4A13		.20	.13	.17	5.0					.30		.57
FAGA105	8832	141.9	143.0	1.1	100	4A13		.19	.17	.18	3.0					.35		.51
FAGA105	8833	143.0	144.0	1.0	100	4E8@		.27	1.18	.98	32.0					2.16		.45
FAGA105	8834	144.8	145.6	.8	100	4E8#	4.06	.30	3.80	3.00	45.0	1.17	7.16	21.10		6.80	28.26	.44
FAGA105	8835	145.6	146.2	.6	100	4L48	3.33	.08	1.50	1.51	18.0	.41	4.50	8.90		3.01	13.40	.50
FAGA105	8836	146.2	146.9	.7	100	4E8*		.26	.46	.50	21.0					.96		.52
FAGA105	8837	146.9	149.0	2.1	100	4A13		.29	.16	.26	11.0					.42		.62
FAGA105	8838	149.0	151.0	2.0	95	4A13		.32	.06	.31	7.0					.37		.84
FAGA105	8839	151.0	153.0	2.0	100	4A13		.36	.05	.25	11.0					.30		.83
FAGA105	8840	153.0	154.1	1.1	100	4C0		.35	.21	.37	12.0					.58		.64
FAGA105	8841	154.1	154.7	.6	100	4DE	3.74	.16	3.40	5.60	48.0	1.37	2.63	14.90		9.00	17.53	.62
FAGA105	8842	166.4	167.2	.8	87	4C0	2.98	.10	.60	1.04	12.0	.21	4.67	6.80		1.64	11.47	.63
FAGA105	8843	167.2	167.8	.6	100	4CL	3.55	.25	1.40	1.17	22.0	.34	8.26	14.70		2.57	22.96	.46
FAGA105	8844	167.8	168.8	1.0	100	4EG8	4.10	.14	5.40	6.00	62.0	.69	3.13	15.00		11.40	18.13	.53
FAGA105	8845	168.8	170.8	2.0	100	4A13	3.25	.15	.35	.29	11.0	.75	2.96	13.50		.64	16.46	.45
FAGA105	8846	170.8	172.6	1.8	100	4A13	3.26	.16	.08	.10	10.0	.89	2.17	15.40		.18	17.57	.56
FAGA105	8847	172.6	173.7	1.1	100	4LE	3.63	.15	2.04	2.30	35.0	1.71	4.08	18.70		4.34	22.78	.53
FAGA105	8848	173.7	175.7	2.0	100	4G8*	2.98	.23	2.40	2.10	36.0	1.17	5.67	20.60		4.50	26.27	.47
FAGA105	8849	175.7	177.2	1.5	100	4G8*	3.93	.25	2.40	2.20	38.0	.62	11.23	21.70		4.60	32.93	.48
FAGA105	8850	177.2	177.6	.4	100	4L5		.52	.66	.65	19.0					1.31		.50
FAGA058	8851	145.4	147.4	2.0	100	4C3	3.93	.25	1.58	.79	28.0	2.54	2.65	27.60		2.37	30.25	.33
FAGA058	8852	147.4	149.4	2.0	35	4C3	3.73	.11	1.80	1.03	29.0	1.58	2.23	25.50		2.83	27.73	.36
FAGA058	8853	149.4	151.5	2.1	76	4C3		.16	.63	.74	20.0					1.37		.54
FAGA058	8854	151.5	152.9	1.4	57	4C3		.31	.32	.49	20.0					.81		.60
FAGA058	8855	152.9	154.7	1.8	72	4C3		.32	.20	.14	14.0					.34		.41
FAGA058	8856	154.7	156.4	1.7	100	4C3		.69	.05	.06	16.0					.11		.55
FAGA058	8857	156.4	157.0	.6	67	4C3		.21	.08	.15	11.0					.23		.65
FAGU045	8858	.0	2.0	2.0	60	4DE4	3.65	.05	5.70	9.10	90.0	1.50	2.36	14.60		14.80	16.96	.61
FAGU045	8859	2.0	4.0	2.0	100	4DE4	3.68	.11	5.90	4.60	69.0	1.85	2.69	16.30		10.50	18.99	.44
FAGU045	8860	4.0	6.0	2.0	100	4DE4	3.62	.08	4.20	5.00	64.0	1.58	2.53	14.70		9.20	17.23	.54
FAGU045	8861	6.0	7.7	1.7	100	4DE4	3.65	.07	5.50	10.20	90.0	1.37	2.49	13.50		15.70	15.99	.65
FAGU045	8862	7.7	8.4	.7	100	5D4	3.29	.05	.53	.51	11.0	.41	9.97	3.88		1.04	13.85	.49
FAGU045	8863	8.4	11.0	2.6	100	4A4	3.50	.03	2.70	6.00	47.0	1.10	2.32	14.50		8.70	16.82	.69
FAGU045	8864	11.0	12.8	1.8	89	4LC	2.98	.02	.16	.29	5.0	.34	3.94	2.22		.45	6.16	.64
FAGU045	8865	12.8	13.7	.9	89	4D4	3.73	.03	6.50	9.30	86.0	1.23	3.39	13.20		15.80	16.59	.59
FAGU045	8866	13.7	16.3	2.6	88	4K4	4.14	.05	2.05	6.40	44.0	.69	4.24	23.90		8.45	28.14	.76
FAGU045	8867	35.1	36.0	.9	89	4K4	3.80	.05	6.20	15.10	107.0	.55	5.70	9.20		21.30	14.90	.71
FAGU045	8868	36.0	36.6	.6	100	4D45	3.79	.18	5.00	5.60	86.0	1.78	2.39	18.10		10.60	20.49	.53

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PC	PY	BAG	PB+ZN	PC+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGU045	8869	36.6	37.6	1.0	70	4A0	3.14	.03	2.06	4.80	36.0	.69	2.06	5.70		6.86	7.76	.70
FAGU045	8870	38.1	39.5	1.4	100	4A4	3.34	.10	3.20	5.60	52.0	.89	5.01	7.90		8.80	12.91	.64
FAGU045	8871	39.5	41.2	1.7	100	4E4	3.25	.14	5.60	5.60	76.0	2.19	1.87	26.40		11.20	28.27	.50
FAGU045	8872	45.7	48.5	2.8	71	4A34	3.71	.08	4.70	5.50	68.0	1.51	1.99	16.70		10.20	18.69	.54
FAGU045	8873	48.5	50.3	1.8	100	4E4	4.51	.10	8.10	14.50	117.0	1.65	1.72	24.20		22.60	25.92	.64
FAGU045	8874	50.3	52.5	2.2	100	4E4	4.88	.12	4.50	6.80	72.0	1.85	1.73	37.30		11.30	39.03	.60
FAGU045	8875	52.5	53.1	.6	83	4G4	4.78	.06	5.90	9.30	88.0	1.03	.87	17.20		15.20	18.07	.61
FAGU045	8876	53.1	54.6	1.5	100	4EG	4.76	.15	7.50	11.90	107.0	1.85	2.84	26.90		19.40	29.74	.61
FAGU045	8877	54.6	56.2	1.6	100	4EG	4.64	.28	2.80	5.10	80.0	1.58	1.54	34.20		7.90	35.74	.65
FAGU045	8878	56.2	57.8	1.6	100	4A1	3.34	.11	1.44	2.90	35.0	.75	1.31	12.20		4.34	13.51	.67
FAGU045	8879	57.8	59.6	1.8	94	4L2	3.06	.06	.33	.85	15.0	.62	2.57	6.00		1.18	8.57	.72
FAGU044	8880	.0	.9	.9	78	4L12	3.06	.07	.52	.65	11.0	.27	4.16	5.50		1.17	9.66	.56
FAGU044	8881	.9	4.0	3.1	100	4A0	3.04	.06	1.48	1.86	24.0	.75	1.18	8.40		3.34	9.58	.56
FAGU044	8882	4.0	6.1	2.1	100	4A14	2.98	.06	2.02	3.20	29.0	.41	.99	4.07		5.22	5.06	.61
FAGU044	8883	6.1	8.1	2.0	90	4A14	3.15	.05	4.30	5.60	52.0	1.17	1.26	6.10		9.90	7.36	.57
FAGU044	8884	8.1	10.2	2.1	100	4A14	3.03	.04	3.80	6.90	47.0	.96	1.41	2.67		10.70	4.08	.64
FAGU044	8885	10.2	12.2	2.0	100	4A0	3.28	.05	1.56	3.20	32.0	.89	1.28	13.50		4.76	14.78	.67
FAGU044	8886	12.2	13.4	1.2	100	4A4	3.69	.08	6.30	8.90	100.0	1.58	1.57	14.90		15.20	16.47	.59
FAGU044	8887	13.4	15.1	1.7	94	4E4	4.45	.07	10.60	17.50	185.0	1.65	2.45	19.20		28.10	21.65	.62
FAGU044	8888	15.1	16.8	1.7	100	4E4	4.86	.09	7.30	14.80	114.0	1.44	1.56	31.30		22.10	32.86	.67
FAGU044	8889	16.8	18.1	1.3	92	4E0	4.78	.19	.95	.98	21.0	.96	1.03	45.30		1.93	46.33	.51
FAGU044	8890	18.1	19.8	1.7	88	4E4	4.25	.12	2.50	3.40	34.0	1.17	3.02	18.80		5.90	21.82	.58
FAGU057	8891	.0	1.8	1.8	61	4D0	3.23	.03	1.92	3.90	41.0	.96	.85	8.30		5.82	9.65	.67
FAGU057	8892	1.8	3.8	2.0	95	4A14	3.04	.03	1.74	3.50	35.0	.82	.68	2.63		5.24	3.31	.67
FAGU057	8893	3.8	5.8	2.0	100	4A1	2.96	.03	.81	1.90	15.0	.69	.60	5.90		2.71	6.50	.70
FAGU057	8894	5.8	7.2	1.4	86	4A1	2.96	.04	1.19	3.00	20.0	.96	1.76	2.80		4.19	4.56	.72
FAGU057	8895	7.2	8.8	1.6	100	4D0	3.18	.07	1.65	4.30	31.0	.82	1.74	8.00		5.95	9.74	.72
FAGU057	8896	11.6	13.2	1.6	75	4D0	3.02	.05	1.74	4.60	28.0	.48	2.30	2.62		6.34	4.92	.73
FAGU057	8897	13.2	15.2	2.0	85	4A1	2.99	.03	1.41	3.30	22.0	.48	1.57	1.12		4.71	2.69	.70
FAGU057	8898	15.2	17.2	2.0	100	4A1	3.00	.04	1.81	.55	35.0	.55	2.22	1.42		2.36	3.64	.23
FAGU057	8899	17.2	19.2	2.0	40	4A14	2.96	.05	1.95	6.30	38.0	1.03	1.74	.85		8.25	2.59	.76
FAGU057	8900	19.2	21.4	2.2	59	4A14	2.96	.03	1.85	3.40	30.0	.62	2.05	2.06		5.25	4.11	.65
FAGA136	8901	122.3	122.9	.6	83	4G4*	4.45	.03	2.40	6.90	49.0	.41	.86	10.10		9.30	10.96	.74
FAGA136	8902	122.9	124.4	1.5	33	5C3	3.46	.06	.93	2.90	32.0	.48	2.56	11.50		3.83	14.06	.76
FAGA136	8903	124.4	126.4	2.0	75	4E4*	4.49	.12	7.90	7.00	96.0	1.03	4.39	28.10		14.90	32.49	.47
FAGA136	8904	126.4	127.7	1.3	100	4D4	3.62	.13	5.10	4.90	73.0	1.23	4.14	15.00		10.00	19.14	.49
FAGA136	8905	127.7	130.5	2.8	25	4C0	3.77	.13	.82	1.12	25.0	1.03	4.46	20.50		1.94	24.96	.58
FAGA136	8906	131.8	132.4	.6	100	4C0	3.57	.05	.99	2.40	29.0	1.92	4.05	18.60		3.39	22.65	.71
FAGA136	8907	132.4	133.8	1.4	100	4A1	3.38	.04	8.30	15.70	133.0	1.23	1.91	9.90		24.00	11.81	.65
FAGA136	8908	135.8	137.1	1.3	92	4C0		.10	.51	1.29	17.0					1.80		.72
FAGA136	8909	137.1	139.0	1.9	47	4A3		.24	.16	.27	11.0					.43		.63
FAGA136	8910	139.0	141.1	2.1	95	4A3		.22	.10	.19	10.0					.29		.66
FAGA136	8911	141.1	143.1	2.0	65	4A3		.27	.11	.18	13.0					.29		.62
FAGA136	8912	145.8	147.5	1.7	94	4C0		.15	.08	.19	7.0					.27		.70
FAGA136	8913	147.5	148.0	.5		4CA		.20	.12	.14	11.0					.26		.54
FAGA136	8914	148.0	150.7	2.7	93	4CA		.40	.05	.05	9.0					.10		.50
FAGA136	8915	150.7	151.2	.5	100	4A2		.07	.11	.18	7.0					.29		.62
FAGA136	8916	151.2	153.1	1.9	63	4A2		.08	1.76	3.20	26.0					4.96		.65
FAGA136	8917	153.1	154.6	1.5	93	4A2		.18	.14	.42	8.0					.56		.75
FAGA136	8918	154.6	156.1	1.5	100	4A2		.17	.25	.52	11.0					.77		.68

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAO	PB+ZN	PO+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGA055	8919	149.0	150.0	1.0	100	4A0	3.04	.07	1.03	2.30	27.0	.55	.99	7.80		3.33	8.79	.69
FAGA055	8920	150.0	150.9	.9	100	4LG	3.28	.06	1.48	1.83	33.0	.55	3.10	10.50		3.31	13.60	.55
FAGA055	8921	150.9	152.9	2.0	95	4A4	3.09	.03	1.87	5.00	35.0	.75	1.71	6.40		6.87	8.11	.73
FAGA055	8922	167.5	168.2	.7	100	4G4#	4.71	.14	7.10	7.90	101.0	1.37	1.75	23.80		15.00	25.55	.53
FAGA055	8923	168.2	169.2	1.0	100	4KL	3.50	.03	2.50	3.80	36.0	.69	3.62	13.90		6.30	17.52	.60
FAGA055	8924	180.7	181.9	1.2	100	4A0	2.99	.03	.85	2.30	19.0	.55	1.12	3.28		3.15	4.40	.73
FAGA055	8925	181.9	182.9	1.0	100	4E4*8	4.46	.21	4.60	3.90	52.0	1.23	4.24	33.30		8.50	37.54	.46
FAGA055	8926	182.9	184.6	1.7	100	4E8#@	4.63	.33	1.11	1.36	22.0	1.37	7.30	35.80		2.47	43.10	.55
FAGAG55	8927	184.6	185.8	1.2	100	4E8#@	4.66	.32	.80	1.00	19.0	1.44	9.85	37.50		1.80	47.35	.56
FAGA055	8928	185.8	187.3	1.5	100	4E8#@	4.43	.25	1.35	1.23	21.0	1.44	6.76	33.70		2.58	40.46	.48
FAGA055	8929	187.3	189.0	1.7	100	4C8	3.65	.37	1.31	1.60	25.0	.96	6.60	20.40		2.91	27.00	.55
FAGA055	8930	189.0	190.8	1.8	100	4C8	3.45	.18	.26	.41	6.0	.82	5.06	19.30		.67	24.36	.61
FAGA055	8931	190.8	192.5	1.7	100	4C8	3.56	.19	1.41	1.20	18.0	.55	8.30	18.50		2.61	26.80	.46
FAGAG55	8932	192.5	194.3	1.8	100	4C8	3.50	.23	1.70	2.40	31.0	1.17	3.87	17.70		4.10	21.57	.59
FAGU041	8933	42.7	44.7	2.0	55	4A1		.08	.38	.48	10.0					.86		.56
FAGU041	8934	44.7	46.7	2.0	95	4A1		.07	.32	.64	11.0					.96		.67
FAGU041	8935	46.7	47.7	1.0	100	4A1		.04	.40	1.23	8.0					1.63		.75
FAGU041	8936	48.4	50.4	2.0	75	4C0		.09	.47	.49	11.0					.96		.51
FAGU041	8937	50.4	52.8	2.4	96	4C0		.08	.30	.38	8.0					.68		.56
FAGU041	8938	52.8	54.8	2.0	100	4A1	2.84	.04	1.70	.67	29.0	.69	1.91	2.77		2.37	4.68	.28
FAGU041	8939	54.8	56.8	2.0	100	4A1	2.98	.04	1.86	3.60	24.0	.62	2.20	2.14		5.46	4.34	.66
FAGU041	8940	56.8	58.8	2.0	100	4A1	3.07	.14	.13	.39	10.0	.89	1.50	4.63		.52	6.13	.75
FAGU041	8941	58.8	60.8	2.0	100	4A1	3.03	.04	1.70	1.00	23.0	.82	1.26	49.40		2.70	50.66	.37
FAGU041	8942	60.8	62.0	1.2	58	4A14	2.96	.20	4.90	6.80	81.0	.62	1.03	.56		11.70	1.59	.58
FAGU041	8943	62.0	63.3	1.3	100	4A14	3.10	.15	7.10	12.00	120.0	.96	1.31	8.60		19.10	9.91	.63
FAGU041	8944	87.8	89.4	1.6	100	4E4*	4.58	.03	1.66	3.60	23.0	1.30	1.24	35.90		5.26	37.14	.68
FAGU041	8945	89.4	91.0	1.6	94	4E4*	4.45	.05	2.80	4.50	36.0	1.65	1.70	30.00		7.30	31.70	.62
FAGU041	8946	91.0	92.1	1.1	100	4K0	4.10	.10	.29	.48	11.0	1.17	2.10	24.90		.77	27.00	.62
FAGU041	8947	92.1	93.5	1.4	71	4A0	3.14	.11	.26	.47	10.0	.82	1.50	11.40		.73	12.90	.64
FAGU040	8948	.0	2.0	2.0	45	4C0	2.99	.04	1.14	1.70	18.0	.41	3.90	5.00		2.84	8.90	.60
FAGU040	8949	2.0	4.0	2.0	45	4C0	3.07	.08	1.76	1.74	29.0	.55	.80	9.10		3.50	9.90	.50
FAGU040	8950	4.0	5.8	1.8	89	4C0	2.96	.06	1.01	.65	17.0	.41	2.10	4.60		1.66	6.70	.39
FAGU034	8951	39.6	40.8	1.2	75	4L12	2.99	.06	4.70	9.80	80.0	.55	1.26	8.00		14.50	9.26	.68
FAGU034	8952	40.8	43.7	2.9	66	4AL	3.04	.09	2.50	3.90	33.0	.62	1.47	11.00		6.40	12.47	.61
FAGU034	8953	43.7	45.2	1.5	73	4L12	3.38	.07	.30	.72	10.0	.48	1.42	9.30		1.02	10.72	.71
FAGU034	8954	45.2	46.8	1.6	87	4L12	3.15	.06	.23	.63	10.0	.41	1.86	7.90		.86	9.76	.73
FAGU034	8955	46.8	48.3	1.5	93	4A3	3.16	.08	1.76	2.80	32.0	.96	1.62	10.80		4.56	12.42	.61
FAGU034	8956	48.3	49.8	1.5	93	4G4#	4.58	.19	7.90	13.60	166.0	1.51	2.21	22.80		21.50	25.01	.63
FAGU034	8957	49.8	51.3	1.5	67	4G4#	4.43	.13	2.10	3.70	97.0	1.17	1.42	26.60		5.80	28.02	.64
FAGU034	8958	51.3	51.9	.6	83	5D4	3.34	.03	1.00	1.02	10.0	.48	2.30	12.60		2.02	14.90	.50
FAGU034	8959	51.9	53.7	1.8	83	4E4	4.57	.26	5.20	7.70	93.0	1.23	1.60	33.50		12.90	35.10	.60
FAGU034	8960	53.7	55.2	1.5	100	4G4#	4.61	.14	4.00	6.80	64.0	1.03	1.06	22.10		10.80	23.16	.63
FAGU034	8961	55.2	56.7	1.5	100	4G4#	4.37	.10	2.60	6.00	52.0	.69	1.57	21.40		8.60	22.97	.70
FAGU034	8962	56.7	58.2	1.5	100	4G4#	4.66	.08	3.30	6.70	54.0	.69	1.82	22.10		10.00	23.92	.67
FAGU034	8963	58.2	59.8	1.6	100	4G4#	4.54	.15	4.70	8.90	68.0	1.03	1.16	23.00		13.60	24.16	.65
FAGU034	8964	59.8	62.7	2.9	90	4E4	4.61	.16	3.50	5.40	60.0	1.03	1.01	33.70		8.90	34.71	.61
FAGU034	8965	62.7	65.0	2.3	91	4G4	4.66	.14	5.70	8.70	100.0	1.37	.61	19.60		14.40	20.21	.60
FAGU034	8966	65.0	67.3	2.3	100	4G4	4.61	.07	2.40	6.70	44.0	.62	.56	22.40		9.10	22.96	.74
FAGU034	8967	67.3	69.7	2.4	96	4G4	4.31	.11	4.80	8.40	80.0	.89	.76	25.40		13.20	26.16	.64
FAGU034	8968	69.7	70.3	.6	100	4L13	2.87	.02	.16	.31	4.0	.21	3.12	2.54		.47	5.66	.66

DDH	SAMPLE	---DEPTHS---	INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAC	PB+ZN	PC+PY	ZN
		FROM	TO	M	%	UNIT	%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGU034	8969	70.3	70.9	.6	100	4D4	4.02	.04	7.80	11.40	103.0	1.78	1.48	19.90	19.20	21.38	.59
FAGU034	8970	70.9	73.8	2.9	100	4GE	4.50	.05	2.80	5.20	50.0	.62	.69	24.80	8.00	25.49	.65
FAGU034	8971	73.8	76.7	2.9	100	4GE	4.33	.08	3.50	6.80	63.0	.75	.65	19.70	10.30	20.35	.66
FAGU034	8972	76.7	79.2	2.5	100	4E4	4.37	.13	3.30	4.50	50.0	1.44	1.29	28.30	7.80	29.59	.58
FAGU034	8973	79.2	80.2	1.0	90	4G4#	4.72	.14	4.00	7.20	69.0	.96	.65	19.20	11.20	19.85	.64
FAGU034	8974	80.2	81.0	.8	100	4E4#	4.76	.14	3.10	4.20	46.0	.89	1.02	38.10	7.30	39.12	.58
FAGU034	8975	81.0	81.9	.9	67	4G4	4.61	.22	5.60	10.50	89.0	1.58	.94	16.30	16.10	17.24	.65
FAGU034	8976	81.9	83.4	1.5	100	4EGD	4.86	.25	5.40	7.00	72.0	1.30	1.13	34.90	12.40	36.03	.56
FAGU034	8977	83.4	84.9	1.5	87	4EGD	4.72	.21	4.40	7.00	66.0	1.44	.98	33.20	11.40	34.18	.61
FAGU034	8978	84.9	86.4	1.5	100	4EGD	4.78	.24	3.80	6.20	69.0	1.44	1.02	35.20	10.00	36.22	.62
FAGU034	8979	86.4	87.9	1.5	100	4EGD	4.33	.18	2.90	5.90	45.0	1.58	1.30	33.90	8.80	35.20	.67
FAGU034	8980	87.9	89.4	1.5	100	4EGD	4.57	.15	8.00	11.40	115.0	1.51	1.02	26.90	19.40	27.92	.59
FAGU034	8981	89.4	90.8	1.4	100	4EGD	4.51	.22	4.30	5.80	66.0	1.65	1.02	34.00	10.10	35.02	.57
FAGU034	8982	90.8	93.3	2.5	92	4D4	4.06	.28	3.50	6.60	58.0	1.65	1.37	25.60	10.10	26.97	.65
FAGU034	8983	93.3	95.7	2.4	100	4EA4	3.69	.12	4.00	7.30	60.0	.96	1.33	16.00	11.30	17.33	.65
FAGU034	8984	95.7	98.1	2.4	92	4EA4	3.80	.09	6.40	8.30	80.0	1.37	2.06	13.40	14.70	15.46	.56
FAGU034	8985	98.1	100.6	2.5	60	4EA0	3.67	.28	.37	.35	15.0	.82	1.68	21.70	.72	23.38	.49
FAGU034	8986	100.6	102.6	2.0	100	4C0		.33	.21	1.46	17.0				1.67		.87
FAGU034	8987	102.6	103.3	.7	100	4AC0		.22	.07	1.22	9.0				1.29		.95
FAGU034	8988	103.3	105.7	2.4	96	4CA		.26	.36	.49	15.0				.85		.58
FAGU034	8989	105.7	108.1	2.4	96	4CA		.27	1.37	1.32	32.0				2.69		.49
FAGAC11	8990	115.5	116.0	.5	100	4C8	3.93	.24	1.90	2.70	39.0	.69	8.70	21.90	4.60	30.60	.59
FAGA011	8991	116.0	116.3	.3	67	4G4	4.49	.07	4.80	9.00	94.0	.69	.40	3.29	13.80	3.69	.65
FAGA011	8992	116.3	116.8	.5	80	4E84	4.53	.15	6.90	4.60	96.0	1.23	1.80	36.30	11.50	38.10	.40
FAGA011	8993	116.8	118.0	1.2	92	4G4	4.51	.07	6.40	8.30	110.0	.62	2.10	13.50	14.70	15.60	.56
FAGA011	8994	119.2	120.4	1.2	100	4E81	3.65	.14	2.05	2.90	35.0	.62	6.60		4.95	6.60	.59
FAGA011	8995	121.6	122.5	.9	100	4E#	3.89	.18	1.77	1.34	38.0	1.37	4.30	25.10	3.11	29.40	.43
FAGA011	8996	133.1	134.3	1.2	92	4LH	3.12	.10	.65	.58	12.0	.34	9.30	4.80	1.23	14.10	.47
FAGA011	8997	211.2	211.8	.6	100	4E#	4.13	.30	1.91	2.40	35.0	1.17	2.90	30.50	4.31	33.40	.56
FAGA011	8998	211.8	212.2	.4	75	4A3	3.60	.25	1.53	1.83	30.0	1.03	4.90	20.60	3.36	25.50	.54
FAGA011	8999	212.2	212.9	.7	71	4E#4	4.20	.17	3.60	3.70	58.0	1.17	3.50	30.20	7.30	33.70	.51
FAGA011	9000	212.9	214.6	1.7	100	4A1	3.31	.19	.42	.76	13.0	.55	5.30	9.90	1.18	15.20	.64
FAGA105	9001	177.6	178.2	.6	100	4C0		.42	.63	.37	18.0				1.00		.37
FAGA105	9002	179.0	180.0	1.0	100	4C8#		.15	.93	.45	21.0				1.38		.33
FAGA105	9003	181.7	182.9	1.2	100	4DA	3.48	.22	1.28	2.70	29.0	1.17	3.72	17.00	3.98	20.72	.68
FAGA105	9004	182.9	183.4	.5	80	4A1		.20	.19	.54	10.0				.73		.74
FAGA105	9005	183.4	185.0	1.6	100	4A13		.20	.21	.27	12.0				.48		.56
FAGA137	9006	96.3	97.7	1.4	100	4A4		.06	2.30	4.60	39.0				6.90		.67
FAGA137	9007	102.9	104.4	1.5	100	4D4	3.76	.07	4.20	6.90	74.0	.89	2.00	8.70	11.10	10.70	.62
FAGA137	9008	104.4	106.6	2.2	100	4A13	2.99	.06	1.71	2.90	30.0	.75	.56	6.70	4.61	7.26	.63
FAGA137	9009	106.6	108.7	2.1	100	4A134	3.31	.05	1.54	3.50	31.0	.69	.66	15.80	5.04	16.46	.69
FAGA137	9010	108.7	110.8	2.1	100	4A13	3.31	.04	1.20	2.60	29.0	.62	.85	3.65	3.80	4.50	.68
FAGA137	9011	110.8	112.9	2.1	100	4A13	2.94	.04	.62	.97	18.0	.48	.53	5.60	1.59	6.13	.61
FAGA137	9012	112.9	115.0	2.1	100	4A13	3.08	.04	1.11	1.89	24.0	.69	.53	8.70	3.00	9.23	.63
FAGA137	9013	115.0	117.1	2.1	90	4A13	2.99	.03	.73	1.04	19.0	.55	.43	6.70	1.77	7.13	.59
FAGA137	9014	117.1	119.2	2.1	100	4A13	3.18	.05	1.17	2.50	27.0	.69	.63	10.80	3.67	11.43	.68
FAGA137	9015	119.2	121.3	2.1	100	4A134	3.23	.05	1.48	4.00	33.0	.82	.76	11.50	5.48	12.26	.73
FAGA109	9016	129.2	131.5	2.3	100	4D4#	3.38	.06	2.90	3.80	46.0	.48	3.09	7.20	6.70	10.29	.57
FAGA109	9017	131.5	134.5	3.0	83	4A0	3.23	.05	1.54	3.20	25.0	.48	1.49	5.50	4.74	6.99	.68
FAGA109	9018	134.5	135.8	1.3	92	4DL4	3.44	.04	3.60	4.90	60.0	.41	1.37	8.70	8.50	10.07	.58

DDH	SAMPLE	---DEPTHS---	INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAO	PB+ZN	PO+PY	ZN
		FROM TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGA109	9019	135.8	138.5	2.7	100	4G4#	4.50	.04	6.90	10.30	104.0	.41	.98	12.00	17.20	12.98	.60
FAGA109	9020	138.5	141.2	2.7	100	4G4#	4.80	.09	5.10	8.00	92.0	.75	1.02	17.20	13.10	18.22	.61
FAGA109	9021	141.2	143.9	2.7	100	4G4#	4.25	.09	5.00	7.20	91.0	.96	.95	15.70	12.20	16.65	.59
FAGA109	9022	143.9	146.5	2.6	100	4G0#	4.67	.11	3.50	5.10	69.0	1.03	1.60	28.10	8.60	29.70	.59
FAGA109	9023	146.5	148.5	2.0	80	4E48	4.63	.10	16.20	10.30	172.0	1.10	6.06	16.20	26.50	22.26	.39
FAGA109	9024	148.5	150.6	2.1	95	4A34	3.31	.09	4.10	4.50	54.0	.96	1.49	10.90	8.60	12.39	.52
FAGA109	9025	155.8	157.9	2.1	100	4CL		.38	.17	.33	13.0				.50		.66
FAGA109	9026	157.9	159.1	1.2	100	4L172		.12	.51	1.22	13.0				1.73		.71
FAGA109	9027	159.1	160.7	1.6	100	4A3		.24	.15	.21	11.0				.36		.58
FAGA109	9028	160.7	161.5	.8	100	4C0		.22	.09	.29	4.0				.38		.76
FAGA109	9029	161.5	164.4	2.9	69	4A3		.12	.18	.21	10.0				.39		.54
FAGU053	9030	.0	1.0	1.0	100	4A34	3.68	.06	1.81	4.60	41.0	1.03	2.40	20.00	6.41	22.40	.72
FAGU053	9031	1.8	3.0	1.2	50	4A134	3.78	.04	2.00	4.40	43.0	.65	3.39	10.00	6.40	13.39	.69
FAGU053	9032	3.0	5.0	2.0	70	4A134	3.34	.04	1.71	4.00	34.0	.89	2.10	13.90	5.71	16.00	.70
FAGU053	9033	5.0	7.0	2.0	100	4A134	3.56	.07	2.70	6.90	49.0	1.23	4.40	14.00	9.60	18.40	.72
FAGU053	9034	7.0	9.1	2.1	100	4A134	3.56	.07	1.86	5.80	43.0	1.17	3.50	16.10	7.66	19.60	.76
FAGU053	9035	9.1	12.2	3.1	65	4A14	2.96	.04	1.49	4.80	28.0	.55	1.80	2.88	6.29	4.68	.76
FAGU053	9036	12.2	15.2	3.0	87	4A14	2.99	.05	2.60	5.40	47.0	.69	1.70	2.47	8.00	4.17	.68
FAGU053	9037	15.2	19.8	4.6	26	4A1	2.98	.04	1.51	3.30	28.0	.55	2.10	4.75	4.21	6.85	.69
FAGU053	9038	28.9	29.9	1.0	100	4A134	3.41	.04	2.30	6.00	45.0	.82	3.20	12.70	8.30	15.90	.72
FAGU053	9039	29.9	31.0	1.1	100	4D0	3.27	.06	2.70	6.20	46.0	.48	4.30	8.40	8.90	12.70	.70
FAGU053	9040	31.0	33.4	2.4	12	5C4*	3.21	.03	.48	.62	10.0	.34	8.40	3.79	1.10	12.19	.56
FAGU053	9041	33.4	34.5	1.1	91	4A14	3.24	.03	2.20	5.20	40.0	.96	3.36	19.20	7.40	22.56	.70
FAGU053	9042	34.5	34.9	.4	100	5C4*	3.00	.03	.16	.68	8.0	.27	5.20	3.80	.84	9.00	.81
FAGU053	9043	34.9	36.0	1.1	100	4L14	2.97	.06	1.93	2.50	30.0	.55	2.30	4.22	4.43	6.52	.56
FAGU053	9044	36.0	37.7	1.7	76	4A1	3.01	.05	2.30	1.45	29.0	.75	1.98	5.56	3.75	7.54	.39
FAGU053	9045	37.7	39.0	1.3	100	4A1	2.96	.06	1.40	2.70	20.0	.41	1.60	2.83	4.10	4.43	.66
FAGU053	9046	39.0	41.1	2.1	100	4A04	3.01	.04	2.30	4.60	38.0	.41	1.93	3.00	6.90	4.93	.67
FAGU053	9047	41.1	42.6	1.5	100	4A14	3.00	.03	1.85	4.70	35.0	.75	1.39	2.16	6.55	3.55	.72
FAGU053	9048	42.6	44.6	2.0	100	4A4	3.13	.05	2.20	4.60	36.0	.75	1.52	8.45	6.80	9.97	.68
FAGU053	9049	44.6	45.7	1.1	82	4E4	4.01	.13	7.20	13.50	124.0	1.58	2.98	15.90	20.70	18.88	.65
FAGU053	9050	1.0	1.8	.8		4L5	3.16	.05	.87	2.70	23.0	.48	3.52	8.90	3.57	12.42	.76
FAGA011	9051	222.1	223.1	1.0	90	4C7	3.68	.19	1.03	1.02	32.0	.27	13.43	12.60	2.05	26.03	.50
FAGA011	9052	223.1	223.7	.6	100	4A1	2.91	.07	.12	.31	7.0	.27	4.64	3.40	.43	8.04	.72
FAGA011	9053	223.7	224.9	1.2	100	4H0	3.72	.17	.42	.45	18.0	.41	13.47	16.40	.87	29.87	.52
FAGA011	9054	224.9	225.6	.7	86	4A1	3.10	.13	.36	.43	15.0	.27	3.69	9.20	.79	12.89	.54
FAGA011	9055	225.6	226.5	.9	56	4A14	3.22	.06	3.80	5.90	60.0	.75	2.76	6.50	9.70	9.26	.61
FAGA011	9056	226.5	227.3	.8	100	4D4	3.34	.10	5.00	8.80	70.0	1.23	2.84	8.00	13.80	10.84	.64
FAGA065	9057	154.2	155.4	1.2	100	4D4	3.97	.12	8.50	16.40	198.0	1.10	2.12	18.30	24.90	20.42	.66
FAGA065	9058	155.4	156.9	1.5	93	4E4	4.54	.09	8.40	11.30	151.0	1.65	1.22	30.40	19.70	31.62	.57
FAGA065	9059	156.9	158.4	1.5	40	4E4	4.26	.26	4.10	5.00	65.0	1.85	1.22	33.50	9.10	34.72	.55
FAGA065	9060	158.4	159.8	1.4	93	4A13	3.59	.12	4.40	9.50	77.0	1.30	1.47	17.20	13.90	18.67	.68
FAGA065	9061	159.8	161.5	1.7	100	4E1	4.08	.28	.26	.63	19.0	1.30	1.35	36.10	.89	37.45	.71
FAGA065	9062	161.5	163.1	1.6	94	4A3	3.64	.14	1.67	2.40	44.0	1.03	1.18	25.10	4.07	26.28	.59
FAGA065	9063	163.1	164.3	1.2	92	4A3	3.43	.13	.81	.97	30.0	1.17	1.14	16.50	1.78	17.64	.54
FAGA149	9064	147.2	148.7	1.5	100	4A1		.24	.15	.39	7.0				.54		.72
FAGA149	9065	161.3	161.7	.4	100	4G4#8	4.50	.08	6.50	6.60	76.0	.89	4.92	20.50	13.10	25.42	.50
FAGA149	9066	161.7	162.6	.9	78	4E0#	4.60	.08	1.55	3.20	27.0	.89	1.18	37.00	4.75	38.18	.67
FAGA149	9067	162.6	164.6	2.0	100	4G4#8	4.40	.19	6.70	6.50	87.0	1.23	2.98	18.40	13.20	21.38	.49
FAGA149	9068	164.6	166.6	2.0	95	4G4#8	4.47	.09	6.10	5.80	77.0	.96	3.38	21.00	11.90	24.38	.49

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAO	PB+ZN	PC+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGA149	9069	166.6	168.6	2.0	100	4G4#8	4.60	.08	6.50	7.30	84.0	1.99	3.78	16.20		13.80	19.98	.53
FAGA149	9070	168.6	170.6	2.0	100	4CE8		.22	.38	.38	14.0					.76		.50
FAGA149	9071	170.6	172.6	2.0	100	4CE8		.32	.11	.18	8.0					.29		.62
FAGA149	9072	172.6	174.6	2.0	100	4CE8		.19	.09	.16	7.0					.25		.64
FAGA149	9073	174.6	176.6	2.0	100	4CE8		.34	.28	.46	13.0					.74		.62
FAGA149	9074	176.6	178.2	1.6	100	4CE8	3.30	.25	1.54	.59	27.0	.62	6.60	13.60		2.13	20.20	.28
FAGA149	9075	178.2	179.7	1.5	100	4DE8	3.36	.23	2.80	2.30	41.0	.34	6.40	13.10		5.10	19.50	.45
FAGA149	9076	179.7	181.3	1.6	94	4CE8		.24	.50	.70	12.0					1.20		.58
FAGA149	9077	181.3	184.4	3.1	100	4CE8		.18	.23	.38	7.0					.61		.62
FAGA149	9078	184.4	186.6	2.2	100	4CE8		.18	.37	1.03	11.0					1.40		.74
FAGA071	9079	119.8	120.6	.8	100	4E4	3.94	.06	7.30	15.60	125.0	1.17	4.48	15.70		22.90	20.18	.68
FAGA071	9080	121.6	122.7	1.1	73	4A4	3.29	.02	3.70	7.80	61.0	.89	1.52	12.00		11.50	13.52	.68
FAGA071	9081	122.7	124.4	1.7	71	4E4	4.64	.04	3.40	6.40	57.0	1.03	.74	33.50		9.80	34.24	.65
FAGAG71	9082	124.4	126.6	2.2	95	4C0	4.29	.06	1.42	2.60	24.0	.62	1.43	5.80		4.02	7.23	.65
FAGAG71	9083	126.6	127.9	1.3	85	4C0	2.96	.04	1.34	2.90	22.0	.41	1.47	4.84		4.24	6.31	.68
FAGA071	9084	127.9	129.5	1.6	94	4C0	2.99	.06	1.15	2.20	21.0	.55	1.35	6.00		3.35	7.35	.66
FAGA071	9085	130.4	131.3	.9	100	4C0	2.99	.07	1.22	2.30	24.0	.55	1.56	5.60		3.52	7.16	.65
FAGAG71	9086	133.0	134.3	1.3	100	4A14	3.12	.03	3.24	4.90	43.0	.69	1.71	2.59		8.14	4.30	.60
FAGAG71	9087	134.3	136.1	1.8	100	4A1	2.65	.02	.73	2.40	16.0	.48	2.54	2.46		3.13	5.00	.77
FAGA071	9088	136.1	137.9	1.8	100	4A1	3.11	.07	1.22	1.70	23.0	.55	2.87	7.10		2.92	9.97	.58
FAGAG71	9089	137.9	139.7	1.8	94	4A1	3.21	.07	1.23	2.70	28.0	.75	.87	8.80		3.93	9.67	.69
FAGA071	9090	140.4	141.1	.7		4A13	3.32	.08	1.46	1.85	33.0	1.10	1.49	14.70		3.31	16.19	.56
FAGAG71	9091	142.8	144.3	1.5	87	4A13		.04	.30	.90	10.0					1.20		.75
FAGA071	9092	146.3	147.3	1.0	100	4A13		.07	.93	1.58	26.0					2.51		.63
FAGA071	9093	148.0	149.2	1.2	33	4A3		.07	.71	1.04	21.0					1.75		.59
FAGA071	9094	159.0	160.9	1.9	100	4A1	3.23	.07	2.30	2.20	38.0	1.03	1.20	5.00		4.50	6.20	.49
FAGA071	9095	160.9	162.8	1.9	95	4A1	3.01	.08	1.45	.92	24.0	.96	.63	6.90		2.37	7.53	.39
FAGA071	9096	162.8	164.6	1.8	100	4A1	3.06	.07	2.80	1.15	45.0	1.17	.73	5.50		3.95	6.23	.29
FAGAG71	9097	164.6	166.5	1.9	89	4A1	3.01	.08	2.50	1.28	37.0	1.44	.53	6.00		3.78	6.53	.34
FAGA071	9098	166.5	168.3	1.8	100	4A1	3.05	.06	2.60	2.03	38.0	1.17	.80	5.00		4.63	5.80	.44
FAGA071	9099	168.3	170.2	1.9	79	4A1	3.16	.08	2.30	1.94	36.0	.89	.87	6.30		4.24	7.17	.46
FAGA071	9100	170.2	172.1	1.9	95	4A1	3.10	.08	2.01	1.19	28.0	1.10	.70	8.10		3.20	8.80	.37
FAGA071	9101	172.1	173.9	1.8	83	4A1	3.25	.09	1.79	1.50	28.0	1.17	.87	8.50		3.29	9.37	.46
FAGAG71	9102	173.9	175.3	1.4	93	4A1	3.01	.09	.38	.69	10.0	1.17	.80	8.70		1.07	9.50	.64
FAGAG71	9103	175.3	175.9	.6	100	4A1	2.91	.06	.35	.21	8.0	.96	.80	6.20		.56	7.00	.38
FAGUG40	9104	6.6	7.9	1.3	100	4A0	2.95	.04	1.76	2.90	27.0	.62	.95	4.39		4.66	5.34	.62
FAGUG40	9105	8.5	10.1	1.6	87	4CA	2.92	.06	1.02	1.36	16.0	.41	1.78	6.80		2.38	8.58	.57
FAGUG40	9106	11.1	12.9	1.8	100	4A0	2.89	.04	1.43	.65	16.0	.62	.59	5.00		2.08	5.59	.31
FAGUG40	9107	17.7	18.6	.9	89	4A0	2.89	.03	1.59	2.50	19.0	.75	.60	2.93		4.09	3.53	.61
FAGUG40	9108	18.6	20.5	1.9	95	4AC	2.94	.03	1.44	1.84	17.0	.82	.63	3.66		3.28	4.29	.56
FAGUG40	9109	21.5	23.5	2.0	95	4A0	3.02	.05	2.50	2.03	28.0	.69	.66	7.50		4.53	8.16	.45
FAGUG40	9110	23.5	25.5	2.0	100	4A0	2.98	.07	2.60	.93	27.0	.82	.40	6.30		3.53	6.70	.26
FAGUG40	9111	25.5	27.5	2.0	100	4A0	2.98	.09	.33	.44	8.0	.82	.53	8.30		.77	8.83	.57
FAGUG40	9112	27.5	29.5	2.0	90	4A0	2.93	.08	.27	.61	7.0	.69	.87	7.30		.88	8.17	.69
FAGUG40	9113	29.5	31.0	1.5	100	4A0	3.06	.11	.13	.36	5.0	.48	1.14	10.90		.49	12.04	.73
FAGUG40	9114	31.0	32.2	1.2	100	4A0	2.96	.09	.08	.24	5.0	.27	2.53	7.40		.32	9.93	.75
FAGUG40	9115	36.3	37.8	1.5	100	4A0	3.10	.08	.29	1.00	8.0	.62	.76	11.30		1.29	12.06	.78
FAGUG40	9116	37.8	39.5	1.7	94	4A0	3.15	.09	1.47	2.70	25.0	.69	.97	8.50		4.17	9.47	.65
FAGUG40	9117	39.5	41.5	2.0	100	4A4	3.26	.08	2.60	3.00	50.0	1.10	1.08	11.70		5.60	12.78	.54
FAGUG40	9118	41.5	43.6	2.1	100	4A0	3.28	.10	.09	.36	7.0	.82	1.04	16.90		.45	17.94	.80

DDH	SAMPLE	---DEPTHS---	INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAO	PB+ZN	PO+PY	ZN
		FROM TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGU040	9119	43.6	45.6	2.0	100	4E4	4.43	.19	5.40	9.60	76.0	1.51	1.37	27.00	15.00	28.37	.64
FAGU040	9120	45.6	46.6	1.0	100	4G4	4.15	.19	5.50	8.10	97.0	1.37	1.92	23.80	13.60	25.72	.60
FAGU040	9121	54.4	56.2	1.8	100	4AG	3.65	.18	2.60	4.70	87.0	1.23	1.12	17.40	7.30	18.52	.64
FAGU040	9122	57.9	59.9	2.0	100	4GE#	4.06	.14	3.40	5.20	69.0	1.37	1.16	25.50	8.60	26.66	.60
FAGU040	9123	59.9	61.9	2.0	100	4GE#	3.97	.05	2.80	5.00	59.0	1.17	1.16	13.50	7.80	14.66	.64
FAGU040	9124	61.9	63.5	1.6	100	4GE#	4.43	.09	5.10	8.90	92.0	1.03	.73	18.40	14.00	19.13	.64
FAGU040	9125	64.6	65.6	1.0	90	4EL	3.59	.13	2.90	3.70	64.0	.75	1.90	15.30	6.60	17.20	.56
FAGU040	9126	65.6	67.6	2.0	95	4GE#	4.08	.10	3.40	6.10	63.0	.82	1.08	17.10	9.50	18.18	.64
FAGU040	9127	67.6	69.6	2.0	100	4GE#	4.29	.15	3.80	6.80	85.0	.96	.95	20.80	10.60	21.75	.64
FAGU040	9128	69.6	71.6	2.0	100	4GE#	4.17	.26	3.50	6.30	105.0	1.30	1.12	23.10	9.80	24.22	.64
FAGU040	9129	71.6	73.0	1.4	100	4GE#	4.38	.21	4.70	7.80	114.0	1.17	.78	20.50	12.50	21.28	.62
FAGU040	9130	73.0	74.7	1.7	53	4GE#	4.33	.16	4.70	7.30	122.0	1.30	.89	22.80	12.00	23.69	.61
FAGU040	9131	85.8	87.8	2.0	80	4A0	3.16	.11	.67	1.25	19.0	.55	7.80	9.00	1.92	16.80	.65
FAGU040	9132	87.8	89.8	2.0	85	4A0	2.98	.12	.16	.94	8.0	.34	5.60	6.10	1.10	11.70	.85
FAGU040	9133	89.8	91.8	2.0	100	4A0	3.02	.23	.26	2.00	15.0	.48	6.00	7.70	2.26	13.70	.88
FAGU040	9134	91.8	93.8	2.0	85	4A0	3.43	.33	1.69	3.10	44.0	.55	6.70	15.00	4.79	21.70	.65
FAGU040	9135	93.8	95.8	2.0	45	4A0	3.28	.07	.47	2.30	16.0	.21	4.20	14.70	2.77	18.90	.83
FAGU040	9136	95.8	97.8	2.0	100	4A0	3.08	.11	.79	1.98	17.0	.14	2.90	9.40	2.77	12.30	.71
FAGU040	9137	97.8	99.0	1.2	100	4A0	2.93	.10	.09	.56	6.0	.21	3.35	6.70	.65	10.05	.86
FAGU040	9138	99.0	100.5	1.5	100	4A0	3.03	.09	.16	.99	8.0	.41	4.39	7.40	1.15	11.79	.86
FAGU040	9139	100.5	102.7	2.2	100	4E4	3.84	.07	4.10	11.40	79.0	.89	5.40	17.10	15.50	22.50	.74
FAGU040	9140	102.7	104.9	2.2	82	4E4	3.76	.17	4.20	5.00	72.0	2.06	2.67	16.00	9.20	18.67	.54
FAGA055	9141	194.3	196.3	2.0	100	4C3		.41	.38	.40	18.0				.78		.51
FAGU028	9142	7.2	9.1	1.9	79	4L0		.05	.53	.34	10.0				.87		.39
FAGU028	9143	9.1	12.4	3.3	42	4L2	3.04	.03	.37	.39	8.0	.21	4.05	5.70	.76	9.75	.51
FAGU028	9144	12.4	14.8	2.4	58	4C3*	3.89	.21	.64	.19	30.0	.96	4.39	27.00	.83	31.39	.23
FAGU028	9145	14.8	16.6	1.8	67	4D384	4.33	.19	6.60	4.30	87.0	1.71	5.06	27.70	10.90	32.76	.39
FAGU028	9146	16.6	17.2	.6	100	4G4#	4.25	.16	7.40	7.10	106.0	.62	2.17	11.00	14.50	13.17	.49
FAGU028	9147	17.2	17.7	.5	80	4L9	3.64	.40	4.10	4.60	61.0	.75	3.65	14.00	8.70	17.65	.53
FAGU028	9148	17.7	19.5	1.8	94	4GE#	4.51	.07	9.70	8.30	136.0	.75	1.62	10.20	18.00	11.82	.46
FAGU028	9149	19.5	21.1	1.6	100	4GE#	4.45	.07	15.80	10.00	170.0	.75	2.75	19.00	25.80	21.75	.39
FAGU028	9150	21.1	22.5	1.4	50	4E1*	3.77	.16	4.70	3.90	65.0	.55	7.43	18.60	8.60	26.03	.45
FAGU057	9151	21.4	22.8	1.4	93	4D0	2.97	.08	3.40	5.70	52.0	.82	1.46	3.53	9.10	4.99	.63
FAGU057	9152	22.8	24.7	1.9	100	4A14	2.86	.03	2.60	5.20	39.0	.55	1.13	1.20	7.80	2.33	.67
FAGU057	9153	24.7	26.7	2.0	35	4A14	2.81	.02	.63	3.40	12.0	.48	.74	.51	4.03	1.25	.84
FAGU057	9154	26.7	28.7	2.0	80	4A14	2.97	.05	3.60	7.10	60.0	.55	2.05	1.81	10.70	3.86	.66
FAGU057	9155	28.7	30.3	1.6	100	4A1	2.80	.01	.82	2.60	15.0	.34	1.09	.24	3.42	1.33	.76
FAGU057	9156	30.3	32.3	2.0	75	4A14	2.96	.02	3.10	5.50	47.0	.48	1.92	.64	8.60	2.56	.64
FAGU057	9157	32.3	34.3	2.0	100	4A1	2.81	.02	1.04	2.60	17.0	.41	1.34	.63	3.64	1.97	.71
FAGU057	9158	34.3	36.3	2.0	100	4A1	2.86	.02	.92	1.52	15.0	.34	1.54	1.19	2.44	2.73	.62
FAGU057	9159	36.3	38.3	2.0	95	4A1	2.91	.02	1.05	1.76	15.0	.41	1.42	1.14	2.81	2.56	.63
FAGU057	9160	38.3	40.3	2.0	95	4A1	2.84	.02	.58	1.07	9.0	.55	1.92	1.21	1.65	3.13	.65
FAGU057	9161	40.3	42.3	2.0	100	4A1	2.79	.01	1.65	1.68	24.0	.41	1.30	.99	3.33	2.29	.50
FAGU057	9162	42.3	44.3	2.0	100	4A1	2.88	.07	.54	.80	11.0	.75	1.46	5.10	1.34	6.56	.60
FAGU057	9163	44.3	46.3	2.0	75	4A1	2.94	.10	.66	.73	14.0	.34	1.79	7.10	1.39	8.89	.53
FAGU057	9164	46.3	48.3	2.0	100	4A1	2.86	.08	.52	.65	10.0	.27	1.55	5.20	1.17	6.75	.56
FAGU057	9165	48.3	50.3	2.0	25	4A1	2.87	.10	.43	.53	9.0	.14	2.10	5.50	.96	7.60	.55
FAGU057	9166	50.3	52.3	2.0	75	4A1	2.96	.12	.64	.57	14.0	.34	2.12	8.10	1.21	10.22	.47
FAGU057	9167	52.3	53.3	1.0	70	4A1	3.01	.03	1.77	1.29	26.0	.55	1.83	3.20	3.06	5.03	.42
FAGU052	9168	.0	3.0	3.0	80	4A14	3.38	.04	1.88	6.10	47.0	.89	2.67	14.70	7.98	17.37	.76

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAC	PB+ZN	PO+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGU052	9169	3.0	5.0	2.0	100	4A14	3.33	.04	1.65	5.30	40.0	1.17	3.91	15.90		6.95	19.81	.76
FAGU052	9170	5.0	7.0	2.0	100	4A14	3.29	.05	2.40	5.50	46.0	.89	2.39	14.20		7.90	16.59	.70
FAGU052	9171	7.0	8.7	1.7	82	4A14	3.16	.03	2.02	5.20	36.0	.75	2.59	8.70		7.22	11.29	.72
FAGU052	9172	8.7	10.6	1.9	95	4A14	2.88	.05	1.74	4.20	64.0	.69	1.88	2.80		5.94	4.68	.71
FAGU052	9173	10.6	13.7	3.1	58	4A1	2.89	.04	1.89	2.60	35.0	.96	1.42	4.77		4.49	6.19	.58
FAGU052	9174	13.7	16.2	2.5	36	4A14	2.95	.06	3.20	3.30	45.0	.82	1.46	5.80		6.50	7.26	.51
FAGU052	9175	19.8	20.8	1.0	100	4A4		.03	4.60	8.60	81.0					13.20		.65
FAGU052	9176	25.9	27.5	1.6	69	4A14	3.18	.09	2.40	4.40	43.0	1.10	2.09	9.80		6.80	11.89	.65
FAGU052	9177	27.5	28.2	.7	100	4L14	3.03	.04	1.55	4.60	32.0	.75	2.29	4.21		6.15	6.50	.75
FAGU052	9178	29.6	30.9	1.3	100	4L14	3.01	.06	2.05	2.74	30.0	.41	2.12	3.90		4.79	6.02	.57
FAGU052	9179	30.9	32.8	1.9	95	4A1	2.97	.07	.93	1.31	15.0	1.17	1.45	7.80		2.24	9.25	.58
FAGU052	9180	32.8	34.8	2.0	100	4A1	2.99	.06	2.70	.96	23.0	1.30	1.11	4.38		3.66	5.49	.26
FAGU052	9181	34.8	35.9	1.1	100	4A14	3.01	.07	3.10	2.94	33.0	.75	1.68	6.00		6.04	7.68	.49
FAGU052	9182	35.9	37.5	1.6	100	4A4	3.10	.12	3.20	4.32	53.0	.89	2.57	8.30		7.52	10.87	.57
FAGU052	9183	37.5	38.9	1.4	100	4AC	3.41	.12	1.62	3.04	35.0	1.37	1.88	16.00		4.66	17.88	.65
FAGU052	9184	38.9	39.4	.5	100	5C*	2.98	.03	.27	.30	5.0	.21	4.61	3.03		.57	7.64	.53
FAGU052	9185	39.4	40.5	1.1	91	4AE	3.61	.15	5.50	9.60	100.0	1.17	4.42	13.20		15.10	17.62	.64
FAGA088	9186	120.1	122.2	2.1	100	4D0	2.92	.05	1.92	3.20	27.0	.62	1.18	1.97		5.12	3.15	.63
FAGA088	9187	122.2	123.7	1.5	100	4C0	2.98	.06	1.50	2.80	18.0	.75	1.20	6.30		4.30	7.50	.65
FAGA088	9188	123.7	125.1	1.4	93	4C0	2.98	.09	1.38	1.80	19.0	.69	1.63	7.40		3.18	9.03	.57
FAGA088	9189	125.1	126.3	1.2	100	4L0	3.03	.04	1.05	3.60	28.0	.21	6.79	3.84		4.65	10.63	.77
FAGA088	9190	126.3	126.8	.5	80	4B4	2.99	.07	1.71	4.80	37.0	.34	4.13	3.25		6.51	7.38	.74
FAGA088	9191	126.8	127.1	.3	100	4L1	2.89	.03	.10	.60	6.0	.21	5.52	2.30		.70	7.82	.86
FAGA088	9192	127.1	128.7	1.6	100	4A3	3.34	.11	1.32	2.80	25.0	1.03	3.34	11.80		4.12	15.14	.68
FAGA088	9193	129.5	129.9	.4	100	4D4	3.52	.05	4.20	7.50	61.0	.89	2.78	11.80		11.70	14.58	.64
FAGA088	9194	134.0	135.3	1.3	100	4E1	4.18	.07	.68	1.58	28.0	.89	3.83	33.50		2.26	37.33	.70
FAGA088	9195	135.3	135.9	.6	100	4AE4	3.85	.04	3.50	6.50	88.0	1.30	1.62	14.40		10.00	16.02	.65
FAGA088	9196	135.9	138.1	2.2	100	4C0	3.75	.12	.90	1.15	32.0	.62	8.51	22.40		2.05	30.91	.56
FAGA088	9197	138.1	139.3	1.2	92	4D4	3.38	.03	4.70	10.20	80.0	.89	1.92	11.80		14.90	13.72	.68
FAGA088	9198	139.3	140.6	1.3	100	4A4	3.46	.10	7.20	14.60	115.0	1.71	2.25	9.20		21.80	11.45	.67
FAGA088	9199	140.6	141.2	.6	100	4D4	3.51	.09	7.90	14.20	119.0	1.37	2.68	8.40		22.10	11.08	.64
FAGA088	9200	141.2	142.9	1.7	94	4A4	3.43	.16	5.50	9.80	90.0	1.37	1.94	11.80		15.30	13.74	.64
FAGA088	9201	142.9	144.5	1.6	100	4A4	3.29	.06	3.50	7.90	59.0	1.03	1.82	10.20		11.40	12.02	.69
FAGA088	9202	144.5	146.2	1.7	94	4A4	3.43	.03	3.20	6.20	51.0	.89	1.09	11.60		9.40	12.69	.66
FAGA088	9203	146.2	147.6	1.4	100	4A4	3.39	.04	3.00	6.20	52.0	.89	1.52	14.80		9.20	16.32	.67
FAGA088	9204	147.6	149.7	2.1	62	4A13	3.32	.08	1.25	3.30	32.0	.89	1.16	17.70		4.55	18.86	.73
FAGA088	9205	149.7	151.7	2.0	95	4A134	3.50	.07	2.40	4.80	49.0	.89	1.42	19.60		7.20	21.02	.67
FAGA088	9206	151.7	153.6	1.9	100	4A134	3.61	.08	1.77	3.80	42.0	1.23	1.47	22.90		5.57	24.37	.68
FAGA088	9207	153.6	155.5	1.9	95	4A134	3.56	.05	1.95	4.20	44.0	1.10	1.48	20.40		6.15	21.88	.68
FAGA088	9208	155.5	157.4	1.9	100	4A134	3.24	.02	1.92	4.80	41.0	.75	1.55	12.00		6.72	13.55	.71
FAGA088	9209	157.4	157.7	.3	100	4L5	2.95	.05	.18	1.15	6.0	.14	5.40	2.46		1.33	7.86	.86
FAGA088	9210	160.9	162.3	1.4	100	5D4*	3.02	.01	.96	2.94	18.0	.27	5.61	4.14		3.90	9.75	.75
FAGA088	9211	166.4	167.8	1.4	100	4A34	3.16	.03	2.06	4.60	42.0	.62	1.42	10.90		6.66	12.32	.69
FAGA088	9212	167.8	169.3	1.5	93	4A3	3.62	.03	1.14	3.50	33.0	.82	1.44	19.60		4.64	21.04	.75
FAGA088	9213	169.3	170.7	1.4	100	4A34	3.50	.05	2.40	5.10	46.0	.75	1.41	15.40		7.50	16.81	.68
FAGA088	9214	176.9	178.4	1.5	100	4H1#4	3.51	.06	4.00	5.20	66.0	.27	9.65	6.45		9.20	16.10	.57
FAGA088	9215	197.8	199.0	1.2	100	4A14	3.42	.04	4.80	10.10	94.0	.41	3.22	8.00		14.90	11.22	.68
FAGA088	9216	199.0	200.3	1.3	15	4A14	3.28	.01	4.70	12.20	97.0	.55	1.45	6.70		16.90	8.15	.72
FAGA088	9217	200.9	201.2	.3	100	4A134	3.12	.04	1.94	3.80	36.0	.55	3.20	8.20		5.74	11.40	.66
FAGA088	9218	210.7	211.3	.6	100	4DE14	4.03	.12	3.20	3.60	50.0	1.71	1.52	24.70		6.80	26.22	.53

DDH	SAMPLE	----DEPTHS----	INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAG	PB+ZN	PC+PY	ZN
		FROM TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGA088	9219	211.3	212.8	1.5	100	4LEH	3.31	.08	1.48	1.40	26.0	.55	3.58	10.50			.49
FAGA088	9220	212.8	214.4	1.6	81	4LEH	3.34	.07	1.72	1.86	33.0	1.03	2.38	14.60	2.88	14.08	.52
FAGA088	9221	214.4	216.2	1.8	100	4E#4	4.91	.21	7.10	12.30	166.0	2.81	1.22	29.80	19.40	31.02	.63
FAGA088	9222	216.2	217.9	1.7	82	4E#4	4.51	.11	7.60	12.90	130.0	1.65	1.40	26.40	20.50	27.80	.63
FAGA088	9223	217.9	218.3	.4	75	4K4	4.07	.04	3.10	4.10	36.0	.82	2.83	22.70	7.20	25.53	.57
FAGA088	9224	218.3	220.0	1.7	100	4E4	4.66	.16	3.90	6.00	65.0	1.58	1.00	36.90	9.90	37.90	.61
FAGA088	9225	220.0	221.7	1.7	100	4E4	4.89	.15	3.10	4.90	61.0	1.30	1.00	38.10	8.00	39.10	.61
FAGA088	9226	221.7	222.8	1.1	100	4A134	3.35	.04	2.60	4.40	42.0	.82	1.66	11.20	7.00	12.86	.63
FAGA088	9227	222.8	223.9	1.1	100	4L127	3.10	.08	.51	.78	12.0	.41	3.99	6.10	1.29	10.09	.60
FAGA088	9228	271.1	272.7	1.6	100	4A1		.07	.06	.22	4.0				.28		.79
FAGA088	9229	272.7	274.4	1.7	94	4A1		.07	.05	.10	5.0				.15		.67
FAGA088	9230	274.4	276.0	1.6	75	4A1		.16	.05	.11	5.0				.16		.69
FAGA088	9231	276.0	277.0	1.0	90	4EA		.14	4.40	8.80	64.0				13.20		.67
FAGA088	9232	277.0	278.6	1.6	100	4A13		.08	.06	.11	4.0				.17		.65
FAGA088	9233	286.1	286.8	.7	86	4LE		.08	.82	.98	10.0				1.80		.54
FAGA088	9234	286.8	288.2	1.4	93	4D8	3.81	.27	2.80	2.90	31.0	.27	13.00	14.30	5.70	27.30	.51
FAGA088	9235	288.2	289.6	1.4	100	4D8	3.83	.20	2.80	3.40	31.0	.01	14.30	14.60	6.20	28.90	.55
FAGA088	9236	299.0	299.9	.9	89	4A13	2.89	.02	.61	1.63	10.0	.21	1.64	1.59	2.24	3.23	.73
FAGA088	9237	299.9	301.1	1.2	25	4DE	3.38	.03	3.30	5.50	59.0	.41	1.92	11.70	8.80	13.62	.62
FAGA088	9238	301.8	303.6	1.8	67	4A14	3.34	.02	1.75	3.80	34.0	.62	1.71	7.50	5.55	9.21	.68
FAGA088	9239	303.6	305.9	2.3	91	4E8	4.56	.32	1.17	1.67	28.0	1.85	4.53	36.30	2.84	40.83	.59
FAGA088	9240	305.9	307.8	1.9	47	4EC	3.94	.34	.43	.28	22.0	2.54	2.37	30.10	.71	32.47	.39
FAGA088	9241	307.8	309.1	1.3	92	4EC	4.30	.32	.85	.70	16.0	1.44	5.20	32.40	1.55	37.60	.45
FAGA088	9242	309.1	310.0	.9	67	4E14	4.04	.18	5.20	4.00	58.0	1.10	10.31	20.90	9.20	31.21	.43
FAGA088	9243	310.0	310.9	.9	56	4C38	3.84	.29	.32	.73	12.0	2.47	3.94	26.30	1.05	30.24	.70
FAGA088	9244	310.9	312.3	1.4	79	4EC	3.86	.30	1.42	1.06	26.0	.82	3.04	23.20	2.48	26.24	.43
FAGA088	9245	312.3	313.6	1.3	92	4EC	4.49	.33	.61	.77	21.0	1.10	2.97	26.70	1.38	29.67	.56
FAGA088	9246	314.9	316.6	1.7	59	4L12		.08	.14	.21	8.0				.35		.60
FAGA088	9247	316.6	318.3	1.7	100	4L12		.21	.05	.07	4.0				.12		.58
FAGA088	9248	318.3	320.0	1.7	47	4L12		.13	.53	.77	13.0				1.30		.59
FAGA088	9249	320.0	321.4	1.4	64	5A1		.02	1.84	2.80	40.0				4.64		.60
FAGA092	9257	49.4	51.5	2.1	57	4D0	3.45	.04	3.70	4.20	56.0	.48	4.19	14.40	7.90	18.59	.53
FAGA092	9258	51.5	53.8	2.3	96	4D4	3.57	.04	10.10	12.80	135.0	1.03	3.41	9.60	22.90	13.01	.56
FAGA092	9259	53.8	55.7	1.9	63	4D4	3.77	.04	5.90	9.60	92.0	.89	2.30	13.30	15.50	15.60	.62
FAGA092	9260	55.7	56.7	1.0	70	4A4	3.56	.18	8.10	14.30	123.0	1.51	5.12	8.40	22.40	13.52	.64
FAGA092	9261	189.6	190.8	1.2	100	4G4*	3.45	.05	4.80	7.60	79.0	.55	2.57	8.00	12.40	10.57	.61
FAGA092	9262	190.8	192.2	1.4	86	4CD	3.49	.14	3.00	2.80	50.0	1.23	1.15	18.70	5.80	19.85	.48
FAGA092	9263	192.2	193.0	.8	100	4G4*	4.50	.22	11.50	10.10	173.0	2.67	1.39	24.50	21.60	25.89	.47
FAGA092	9264	193.0	194.4	1.4	100	4L2	3.16	.05	1.31	1.72	36.0	.69	2.07	9.30	3.03	11.37	.57
FAGA141	9266	43.3	45.3	2.0	25	4A0	2.77	.03	1.03	.55	23.0	.27	.51	1.05	1.58	1.56	.35
FAGA141	9267	45.3	47.3	2.0	90	4A4	3.01	.06	1.64	3.60	31.0	.69	.80	8.00	5.24	8.80	.69
FAGA141	9268	47.3	49.3	2.0	85	4A0	2.84	.04	1.33	3.20	25.0	.48	.67	2.98	4.53	3.65	.71
FAGA141	9269	49.3	51.3	2.0	100	4A0	3.01	.06	1.38	3.20	29.0	.55	.75	9.50	4.58	10.25	.70
FAGA141	9270	51.3	53.3	2.0	100	4A0	3.02	.05	1.35	3.20	29.0	.62	.87	5.00	4.55	5.87	.70
FAGA141	9271	53.3	55.5	2.2	100	4A0	2.93	.04	1.42	3.10	27.0	.48	.88	5.10	4.52	5.98	.69
FAGA141	9272	55.8	57.1	1.3	100	4B4	3.01	.02	1.38	5.00	30.0	.34	3.64	5.60	6.38	9.24	.78
FAGA141	9273	57.1	57.6	.5	80	4E4	4.05	.35	5.60	12.60	154.0	2.54	2.09	20.50	18.20	22.59	.69
FAGA141	9274	58.6	60.8	2.2	100	4C0	3.33	.04	1.00	3.00	27.0	.21	6.91	7.80	4.00	14.71	.75
FAGA141	9275	65.6	66.6	1.0	100	4L24	3.17	.02	.55	.84	17.0	.27	4.32	8.20	1.39	12.52	.60

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAO	PB+ZN	PO+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGA141	9276	68.5	69.7	1.2	100	4E4	4.40	.18	12.30	18.70	166.0	2.26	1.16	21.10		31.00	22.26	.60
FAGA141	9277	69.7	70.4	.7	100	4A14	3.34	.06	5.80	9.10	88.0	1.10	2.08	11.00		14.90	13.08	.61
FAGA141	9278	70.4	71.0	.6	100	4D0	3.12	.06	3.50	5.10	53.0	.82	2.88	8.60		8.60	11.48	.59
FAGA141	9279	71.0	73.0	2.0	100	4A4	2.92	.03	1.85	4.50	42.0	.55	1.40	3.40		6.35	4.80	.71
FAGA141	9280	73.0	75.0	2.0	100	4A4	3.07	.02	1.83	4.60	40.0	.69	1.88	3.65		6.43	5.53	.72
FAGA141	9281	75.0	76.7	1.7	100	4A0	2.93	.02	1.25	1.62	20.0	.48	2.16	3.57		2.87	5.73	.56
FAGA141	9282	77.6	79.6	2.0	95	4A4	3.39	.05	4.70	8.30	66.0	1.10	1.62	12.40		13.00	14.02	.64
FAGA141	9283	79.6	80.2	.6	100	4E4	3.90	.04	10.40	17.10	170.0	2.33	2.32	22.30		27.50	24.62	.62
FAGA141	9284	80.5	81.4	.9	100	4E4	4.38	.05	8.40	14.80	146.0	1.65	2.36	23.60		23.20	25.96	.64
FAGA141	9285	81.4	81.8	.4	100	4A4	3.68	.08	6.40	9.90	97.0	1.30	1.95	17.20		16.30	19.15	.61
FAGA141	9286	82.4	83.4	1.0	100	4A4	3.56	.04	5.30	9.40	90.0	1.10	1.86	15.20		14.70	17.06	.64
FAGA141	9287	83.5	84.2	.7	100	4A4	3.34	.05	3.40	4.80	59.0	1.37	1.74	13.90		8.20	15.64	.59
FAGA141	9288	84.4	84.8	.4	100	4A4	3.43	.06	3.50	3.00	61.0	1.44	1.45	15.90		6.50	17.35	.46
FAGA141	9289	84.8	85.7	.9	100	4E4	4.83	.07	9.60	13.80	178.0	.48	1.74	24.90		23.40	26.64	.59
FAGA141	9290	85.7	86.9	1.2	42	4A4	3.44	.03	5.40	8.50	100.0	1.65	1.52	11.20		13.90	12.72	.61
FAGA141	9291	86.9	87.3	.4	100	4E4	4.63	.05	8.00	10.80	161.0	1.44	2.20	27.30		18.80	29.50	.57
FAGA141	9292	87.3	88.3	1.0	100	4A4	3.64	.15	6.30	8.80	100.0	1.03	2.12	12.10		15.10	14.22	.58
FAGA141	9293	88.5	88.9	.4	100	4D4	3.60	.11	5.10	8.10	87.0	1.23	4.28	12.00		13.20	16.28	.61
FAGA141	9294	89.1	89.8	.7	100	4A4	3.42	.04	3.40	7.40	58.0	1.03	2.87	12.10		10.80	14.97	.69
FAGA141	9295	77.0	77.6	.6	100	4C0	3.45	.04	.59	3.10	18.0	.75	3.66	17.30		3.69	20.96	.84
FAGA157	9296	32.7	33.3	.6	100	4E#4	4.20	.15	3.90	3.20	62.0	.07	3.76	26.40		7.10	30.16	.45
FAGA157	9297	33.3	34.1	.8	100	4Q2	3.41	.07	2.50	2.30	45.0	.07	12.10	7.00		4.80	19.10	.48
FAGA157	9299	70.9	72.6	1.7	100	4CL#	3.71	.25	1.07	1.10	25.0	.55	5.05	21.40		2.17	26.45	.51
FAGA157	9300	72.6	74.6	2.0	100	4C3	4.18	.15	2.30	.77	34.0	.96	3.52	29.30		3.07	32.82	.25
FAGU028	9301	56.7	58.3	1.6	94	4E4	4.50	.15	7.80	12.30	146.0	1.17	1.25	26.00		20.10	27.25	.61
FAGU028	9302	58.3	60.5	2.2	82	4E4	4.84	.23	6.70	11.10	125.0	1.58	4.10	28.80		17.80	32.90	.62
FAGU028	9303	60.5	62.3	1.8	100	4E4	4.49	.21	7.20	13.00	112.0	1.51	7.09	21.60		20.20	28.69	.64
FAGUC28	9304	62.3	64.0	1.7	100	4E4	4.61	.31	5.90	11.10	110.0	2.40	6.37	27.30		17.00	33.67	.65
FAGA090	9305	49.2	50.5	1.3	100	4B4	3.02	.04	2.60	5.20	49.0	.55	3.56	3.27		7.80	6.83	.67
FAGA090	9306	50.5	51.7	1.2	100	4B4	2.93	.04	2.00	4.50	41.0	.55	3.13	2.56		6.50	5.69	.69
FAGA090	9307	51.7	53.6	1.9	100	5C4*	2.94	.01	.12	1.20	8.0	.21	7.27	1.43		1.32	8.70	.91
FAGA090	9308	53.6	55.0	1.4	100	4B4	2.96	.07	1.85	4.30	38.0	.89	2.73	3.94		6.15	6.67	.70
FAGA090	9309	55.0	56.4	1.4	100	4B4	2.93	.02	.89	3.40	23.0	.34	4.55	2.04		4.29	6.59	.79
FAGA090	9310	57.7	59.4	1.7	94	4B4	2.96	.02	1.96	5.00	38.0	1.37	3.55	3.62		6.96	7.17	.72
FAGA090	9311	59.4	61.2	1.8	94	4B4	2.96	.02	1.45	4.10	30.0	.89	3.58	4.22		5.55	7.80	.74
FAGAC90	9312	62.1	63.5	1.4	71	4B4	3.03	.10	2.02	4.50	40.0	.62	3.38	6.40		6.52	9.78	.69
FAGAC90	9313	63.7	64.7	1.0	100	4B4	2.97	.02	1.49	4.30	30.0	.55	3.03	4.87		5.79	7.90	.74
FAGA090	9314	64.7	66.8	2.1	86	4A4	3.02	.04	1.13	3.20	24.0	2.13	2.72	2.96		4.33	5.68	.74
FAGA090	9315	68.5	69.7	1.2	67	4L0	3.33	.02	.97	1.80	22.0	.27	8.19	11.70		2.77	19.89	.65
FAGA090	9316	70.2	72.5	2.3	100	5A69	3.23	.03	.95	1.81	24.0	.41	6.00	9.60		2.76	15.60	.66
FAGA090	9317	268.8	269.9	1.1	82	4L0	3.00	.02	.81	.58	17.0	.27	2.93	2.90		1.39	5.83	.42
FAGAC90	9318	77.4	79.0	1.6	69	4LE4	3.16	.02	3.48	6.20	55.0	.48	3.06	6.50		9.68	9.56	.64
FAGA090	9319	79.0	80.6	1.6	94	4LE4	3.34	.02	.88	1.35	21.0	.41	2.06	16.10		2.23	18.16	.61
FAGAC90	9320	80.6	82.1	1.5	100	4E14	3.79	.15	6.80	7.90	107.0	1.58	2.20	19.10		14.70	21.30	.54
FAGA090	9321	82.1	82.7	.6	100	4D43	3.18	.08	3.40	5.40	51.0	.41	1.67	9.50		8.80	11.17	.61
FAGA090	9322	82.7	83.4	.7	100	5C4*	3.05	.01	.15	4.90	6.0	.21	6.25	4.30		5.05	10.55	.97
FAGAC90	9323	83.4	85.2	1.8	100	4A14	3.02	.04	2.50	5.10	41.0	.41	1.51	5.40		7.60	6.91	.67
FAGA090	9324	85.2	87.0	1.8	100	4A14	3.02	.02	1.70	3.90	34.0	.48	1.56	7.30		5.60	8.86	.70
FAGAC90	9325	87.0	88.9	1.9	100	4A14	3.30	.03	3.20	6.20	51.0	.89	3.19	6.20		9.40	9.39	.66
FAGA090	9326	88.9	89.6	.7	100	4L0	3.05	.02	.86	1.87	16.0	.27	3.24	6.50		2.73	9.74	.68

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAO	PB+ZN	PG+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGA090	9327	89.6	90.1	.5	100	4C0	3.54	.07	2.90	3.30	47.0	.75	3.09	19.20		6.20	22.29	.53
FAGA090	9328	90.1	91.7	1.6	94	4A14	3.52	.05	2.40	3.00	42.0	1.23	1.52	18.90		5.40	20.42	.56
FAGA090	9329	91.7	93.3	1.6	100	4A14	3.45	.10	5.00	6.10	73.0	1.44	1.95	11.80		11.10	13.75	.55
FAGA090	9330	93.3	94.8	1.5	100	4A14	3.41	.02	3.60	6.20	60.0	1.03	2.39	11.20		9.80	13.59	.63
FAGA090	9331	94.8	96.6	1.8	89	5B6	3.08	.02	.40	.50	8.0	.27	2.25	3.59		.90	5.84	.56
FAGA090	9332	96.6	97.8	1.2	100	4A14	3.48	.03	4.00	4.80	61.0	1.10	1.77	12.00		8.80	13.77	.55
FAGAG90	9333	97.8	99.0	1.2	100	4A14	3.88	.11	3.00	3.80	59.0	1.30	1.56	18.00		6.80	19.56	.56
FAGAG90	9334	99.0	99.7	.7	100	4D0	3.47	.03	2.90	3.70	42.0	.55	1.97	13.20		6.60	15.17	.56
FAGAG90	9335	99.7	101.9	2.2	100	5D*	3.20	.01	.43	1.47	10.0	.27	9.45	1.94		1.90	11.39	.77
FAGAG90	9336	101.9	103.3	1.4	100	4D0	3.34	.06	2.90	5.40	49.0	.96	1.49	8.70		8.30	10.19	.65
FAGAG90	9337	103.3	104.1	.8	100	5D*	3.35	.09	1.94	4.10	31.0	.41	6.92	5.40		6.04	12.32	.68
FAGAG90	9338	104.1	106.3	2.2	91	4A4	3.49	.06	5.00	8.60	72.0	1.03	2.80	6.90		13.60	9.70	.63
FAGAG90	9339	106.3	108.5	2.2	95	4A4	3.48	.03	5.80	12.90	90.0	1.03	3.31	6.70		18.70	10.01	.69
FAGAG90	9340	206.0	207.4	1.4	100	4L2		.04	3.80	5.00	67.0					8.80		.57
FAGA090	9341	213.8	214.5	.7	100	4A4	3.23	.05	2.70	4.40	37.0	.34	4.39	5.40		7.10	9.79	.62
FAGAG90	9342	214.5	215.4	.9	100	4E#4	3.86	.07	7.30	12.10	103.0	.62	3.37	16.30		19.40	19.67	.62
FAGA090	9343	215.4	216.0	.6	83	4L14	2.92	.02	2.50	3.00	39.0	.41	.72	4.46		5.50	5.18	.55
FAGA090	9344	216.0	216.4	.4	75	4G*A	3.68	.02	4.90	9.30	65.0	.48	1.50	10.50		14.20	12.00	.65
FAGAG90	9345	216.4	218.3	1.9	100	4A14	2.95	.01	1.78	3.60	26.0	.34	1.43	2.34		5.38	3.77	.67
FAGA090	9346	264.7	265.0	.3	100	4A14	3.08	.07	1.47	2.80	27.0	.48	2.41	7.60		4.27	10.01	.66
FAGA090	9347	265.0	265.7	.7	100	4EH	4.57	.06	5.30	5.90	72.0	.48	16.09	17.90		11.20	33.99	.53
FAGA090	9348	265.7	266.1	.4	100	4G#	3.43	.14	4.20	5.90	62.0	.27	4.21	9.90		10.10	14.11	.58
FAGA090	9349	266.1	267.5	1.4	93	4LE	3.14	.07	.80	.63	18.0	.27	5.56	6.50		1.43	12.06	.44
FAGA090	9350	267.5	268.8	1.3	100	4E#4	3.89	.11	2.90	3.70	49.0	.62	2.49	23.60		6.60	26.09	.56
FAGAG90	9351	269.9	270.9	1.0	80	4E4	4.34	.08	11.90	6.00	131.0	.89	12.29	15.40		17.90	27.69	.34
FAGA090	9352	270.9	271.8	.9	100	4E0	4.47	.29	6.10	3.70	79.0	1.51	6.16	29.80		9.80	35.96	.38
FAGA090	9353	271.8	273.0	1.2	100	4E#4	3.85	.20	3.90	5.30	62.0	1.03	3.35	21.50		9.20	24.85	.58
FAGU039	9354	.0	1.5	1.5	80	4CL	2.99	.04	2.10	1.52	30.0	.48	2.73	5.40		3.62	8.13	.42
FAGU039	9355	1.5	2.8	1.3	46	4C0	3.02	.05	.41	.90	8.0	.48	3.47	6.60		1.31	10.07	.69
FAGU039	9356	2.8	4.1	1.3	100	4C0	3.10	.15	2.10	1.52	33.0	.55	2.29	8.20		3.62	10.49	.42
FAGU039	9357	6.2	8.4	2.2	100	4A1	2.95	.04	1.38	.32	17.0	.82	2.75	4.00		1.70	6.75	.19
FAGU039	9358	8.4	9.7	1.3	100	4C0	2.92	.03	2.00	2.90	29.0	.41	1.64	.85		4.90	2.49	.59
FAGU039	9359	9.7	11.0	1.3	100	4C0	3.06	.07	1.33	2.50	25.0	.75	1.90	4.01		3.83	5.91	.65
FAGU039	9360	15.5	16.1	.6	83	4LC	2.89	.03	1.84	2.06	29.0	.34	1.93	1.65		3.90	3.58	.53
FAGU039	9361	16.5	17.9	1.4	43	4AL	2.91	.02	.40	1.20	8.0	.14	3.56	1.96		1.60	5.52	.75
FAGU039	9362	18.3	19.4	1.1	100	4CL	2.89	.03	1.70	3.00	25.0	.21	3.07	2.54		4.70	5.61	.64
FAGU039	9363	20.8	22.8	2.0	100	4A4	3.06	.04	2.37	4.80	33.0	.69	1.57	6.00		7.17	7.57	.67
FAGU039	9364	23.3	25.9	2.6	100	4LC	2.95	.03	.77	1.56	12.0	.55	.57	4.91		2.33	5.48	.67
FAGU039	9365	25.9	28.0	2.1	100	4A1	2.91	.04	1.53	.88	14.0	.62	.11	4.62		2.41	4.73	.37
FAGU039	9366	28.8	29.7	.9	100	4CL	2.90	.03	1.97	2.90	26.0	.55	2.80	2.33		4.87	5.13	.60
FAGU039	9367	35.9	36.7	.8	75	4CL	2.96	.03	1.71	1.27	22.0	.27	2.87	5.40		2.98	8.27	.43
FAGU039	9368	37.3	37.9	.6	83	4CL	2.92	.03	.54	1.03	10.0	.07	3.53	3.69		1.57	7.22	.66
FAGU039	9369	38.7	40.9	2.2	100	4CL	2.96	.05	.45	1.50	13.0	.07	4.97	4.03		1.95	9.00	.77
FAGU039	9370	42.7	44.2	1.5	87	4EG	4.35	.16	7.50	14.70	116.0	.96	2.53	24.20		22.20	26.73	.66
FAGU039	9371	48.8	49.3	.5	100	4E0	4.18	.01	1.30	2.90	28.0	.55	.79	31.20		4.20	31.99	.69
FAGU039	9372	50.7	53.0	2.3	100	4E46	4.34	.11	4.70	7.10	88.0	1.03	1.46	25.90		11.80	27.36	.60
FAGU039	9373	53.0	54.9	1.9	100	4G4*	4.66	.20	5.10	9.20	81.0	1.44	.47	14.90		14.30	15.37	.64
FAGU039	9374	54.9	56.4	1.5	100	4E46	4.53	.26	6.80	12.10	74.0	1.65	2.52	27.10		18.90	29.62	.64
FAGU039	9375	56.4	57.9	1.5	100	4E46	4.66	.19	4.10	6.30	62.0	1.23	1.95	37.80		10.40	39.75	.61
FAGU039	9376	57.9	59.2	1.3	92	4G4	4.93	.14	3.80	7.70	69.0	1.51	1.50	19.80		11.50	21.30	.67

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAO	PB+ZN	PC+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGU039	9377	59.2	60.5	1.3	100	4G4	4.60	.22	4.10	7.60	74.0	1.44	2.01	28.40		11.70	30.41	.65
FAGU039	9378	60.5	61.0	.5	80	4C3	3.52	.11	1.18	2.90	25.0	.75	2.73	19.30		4.08	22.03	.71
FAGU039	9379	61.0	62.5	1.5	100	4E4	4.72	.22	2.90	4.10	42.0	1.44	2.89	37.80		7.00	40.69	.59
FAGU039	9380	62.5	64.0	1.5	100	4E4	4.24	.15	2.30	2.90	41.0	1.78	2.12	34.20		5.20	36.32	.56
FAGU039	9381	65.9	67.9	2.0	95	4E4	4.34	.21	3.20	3.00	66.0	2.06	2.09	32.20		6.20	34.29	.48
FAGU039	9382	67.9	70.2	2.3	100	4E4	4.40	.15	3.00	3.50	47.0	6.84	1.08	31.80		6.50	32.88	.54
FAGU039	9383	72.6	73.2	.6	100	4LD	4.49	.05	4.40	7.60	67.0	.89	3.13	5.80		12.00	8.93	.63
FAGU039	9384	73.2	75.2	2.0	100	4CG	3.91	.04	2.40	5.90	46.0	.62	.63	16.20		8.30	16.83	.71
FAGU039	9385	75.2	77.2	2.0	90	4CG	3.63	.05	2.50	5.10	47.0	.62	.21	15.00		7.60	15.21	.67
FAGU039	9386	77.2	79.2	2.0	100	4CG	3.91	.16	3.10	6.80	86.0	1.37	.55	13.40		9.90	13.95	.69
FAGU039	9387	79.2	81.2	2.0	100	4CG	3.62	.05	3.30	6.80	49.0	.69	.77	10.60		10.10	11.37	.67
FAGU039	9388	81.2	83.4	2.2	100	4D43	4.03	.03	8.70	18.00	151.0	1.58	2.09	12.90		26.70	14.99	.67
FAGU039	9389	83.4	84.8	1.4	100	4E4	4.81	.29	5.20	8.40	77.0	1.92	1.03	33.30		13.60	34.33	.62
FAGU039	9390	84.8	85.4	.6	100	4G4*6	4.49	.31	6.70	12.30	105.0	2.61	1.20	27.20		19.00	28.40	.65
FAGU039	9391	85.4	87.4	2.0	100	4E4	4.51	.20	4.70	8.20	63.0	1.71	2.22	30.90		12.90	33.12	.64
FAGU039	9392	87.4	89.4	2.0	100	4E4	4.63	.21	2.70	4.90	49.0	1.44	1.80	37.90		7.60	39.70	.64
FAGU039	9393	89.4	91.2	1.8	100	4E0	4.57	.28	1.10	2.20	29.0	1.37	1.70	37.40		3.30	39.10	.67
FAGU039	9394	91.2	93.2	2.0	100	4DE	3.99	.31	3.50	4.40	58.0	1.71	2.27	25.50		7.90	27.77	.56
FAGU039	9395	93.2	95.2	2.0	100	4DE	4.04	.21	2.40	1.35	37.0	1.10	9.25	17.40		3.75	26.65	.36
FAGU039	9396	95.2	96.7	1.5	100	4DA	4.01	.14	4.40	10.54	68.0	2.67	5.34	15.10		14.94	20.44	.71
FAGA116	9397	110.9	112.5	1.6	100	4A13	3.16	.05	1.60	3.08	29.0	.75	1.03	10.50		4.68	11.53	.66
FAGA116	9398	112.5	114.1	1.6	100	4A13	3.13	.03	1.50	3.18	27.0	.55	1.10	7.60		4.68	8.70	.68
FAGA139	9399	122.5	123.0	.5	100	4D45	3.47	.17	4.30	8.02	70.0	.55	1.66	8.00		12.32	9.66	.65
FAGA139	9400	123.0	124.6	1.6	100	4G4#	3.80	.06	7.10	11.12	105.0	.75	2.46	13.90		18.22	16.36	.61
FAGA139	9401	124.6	125.4	.8	100	4E10	4.56	.04	1.20	2.50	31.0	.82	1.08	41.30		3.70	42.38	.68
FAGA139	9402	125.4	127.4	2.0	100	4A4	3.08	.03	1.80	3.86	32.0	.62	1.23	.66		5.66	1.89	.68
FAGA139	9403	127.4	129.4	2.0	90	4A0	3.01	.03	1.00	3.00	20.0	.48	1.29	8.30		4.00	9.59	.75
FAGA139	9404	129.4	131.7	2.3	70	4A4	3.14	.04	1.70	3.90	31.0	.55	1.56	9.20		5.60	10.76	.70
FAGA117	9405	80.8	81.2	.4	100	4G4	4.47	.18	5.60	11.50	100.0	1.37	1.16	20.20		17.10	21.36	.67
FAGA117	9406	81.2	83.1	1.9	100	4D4	4.18	.14	12.30	19.60	210.0	2.26	2.35	10.40		31.90	12.75	.61
FAGA117	9407	83.1	85.2	2.1	100	4A4	3.66	.06	8.70	19.00	171.0	1.10	3.06	7.10		27.70	10.16	.69
FAGA117	9408	85.2	86.0	.8	87	4E14	4.17	.13	9.90	19.60	206.0	2.13	2.72	13.70		29.50	16.42	.66
FAGA117	9409	86.0	87.8	1.8	100	4E4	4.66	.22	6.00	8.50	104.0	1.65	1.67	28.80		14.50	30.47	.59
FAGA117	9410	87.8	89.6	1.8	100	4G4	4.61	.18	5.90	10.90	103.0	1.51	1.28	14.80		16.80	16.08	.65
FAGA117	9411	97.1	97.4	.3	100	4G4	4.45	.05	3.50	7.30	76.0	1.03	1.13	11.60		10.80	12.73	.68
FAGA117	9412	97.4	98.1	.7	100	4E64#	4.81	.18	4.70	8.60	102.0	1.03	2.00	23.50		13.30	25.50	.65
FAGA117	9413	99.1	101.2	2.1	100	4E#4	4.63	.24	5.10	8.70	102.0	.96	1.78	31.30		13.80	33.08	.63
FAGA117	9414	101.2	103.3	2.1	100	4E#4	4.37	.18	4.50	6.50	86.0	1.03	1.96	26.40		11.00	28.36	.59
FAGA117	9415	150.3	150.9	.6	100	4DE4	3.56	.13	4.20	4.90	70.0	1.71	1.76	13.00		9.10	14.76	.54
FAGA117	9416	151.3	152.4	1.1	100	4D73	3.69	.22	3.70	6.00	63.0	2.88	5.17	13.30		9.70	18.47	.62
FAGA117	9417	152.4	153.8	1.4	100	4C0	3.36	.27	.82	1.59	42.0	1.44	3.16	14.60		2.41	17.76	.66
FAGA117	9418	153.8	155.2	1.4	100	4C0	3.46	.20	1.20	1.26	30.0	2.26	2.83	18.00		2.46	20.83	.51
FAGA117	9419	155.2	156.4	1.2	100	4D4	3.66	.14	5.30	5.90	81.0	1.92	2.34	16.80		11.20	19.14	.53
FAGA117	9420	156.4	157.9	1.5	20	4D4	3.75	.15	6.40	11.90	101.0	2.54	3.15	12.50		18.30	15.65	.65
FAGA066	9421	51.2	52.6	1.4	100	4A0	3.04	.04	1.71	3.00	35.0	.27	3.98	6.50		4.71	10.48	.64
FAGA066	9422	52.6	53.9	1.3	100	4A0	3.14	.09	1.37	3.00	32.0	.21	6.60	6.80		4.37	13.40	.69
FAGA066	9423	61.7	63.4	1.7	100	4A0	3.20	.09	.95	2.30	23.0	.34	4.57	9.10		3.25	13.67	.71
FAGA066	9424	64.4	66.4	2.0	100	4A4	3.24	.05	2.05	3.00	45.0	.55	2.70	6.20		5.05	8.90	.59
FAGA066	9425	66.4	68.3	1.9	95	4A0	3.19	.08	1.17	3.10	25.0	.62	3.17	10.00		4.27	13.17	.73
FAGA066	9426	82.0	83.5	1.5	100	4E4	4.51	.07	4.90	9.50	79.0	.75	3.17	25.40		14.40	28.57	.66

DCH	SAMPLE	---DEPTHS---		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAC	PB+ZN	PC+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGAG66	9427	83.5	85.0	1.5	100	4E4	4.61	.07	6.10	14.10	101.0	.96	3.21	25.40		20.20	28.61	.70
FAGAG66	9428	85.0	86.9	1.9	95	4043	3.84	.12	5.90	7.90	81.0	1.03	1.21	14.70		13.80	15.91	.57
FAGAG66	9429	86.9	88.6	1.7	53	4A34	3.45	.18	5.20	5.00	83.0	1.37	1.06	20.60		10.20	21.66	.49
FAGAG66	9430	89.5	91.2	1.7	94	4A13	3.24	.12	.38	.93	16.0	.48	1.21	14.60		1.31	15.81	.71
FAGAG66	9431	91.2	93.0	1.8	72	4A13	3.02	.14	.46	1.07	18.0	.41	1.41	10.00		1.53	11.41	.70
FAGAG66	9432	93.0	93.3	.3	100	50\$	2.95	.03	.13	2.60	3.0	.27	5.44	3.18		2.73	8.62	.95
FAGAG66	9433	93.3	95.1	1.8	22	4A0	3.13	.10	.58	1.31	18.0	.41	1.94	12.00		1.89	13.94	.69
FAGAG66	9434	95.1	97.1	2.0	45	4A0	3.15	.10	1.00	1.00	25.0	.34	5.20	10.80		2.00	16.00	.50
FAGAG66	9435	97.1	98.6	1.5	67	4L12	3.12	.07	.35	3.50	10.0	.14	7.20	6.60		3.85	13.80	.91
FAGAG66	9436	98.6	100.1	1.5	60	4L12	3.01	.08	.46	1.68	11.0	.14	3.83	6.90		2.14	10.73	.79
FAGAG66	9437	100.1	101.9	1.8	50	4A0	2.99	.10	.21	.29	6.0	.55	.73	10.30		.50	11.03	.58
FAGAG66	9438	101.9	103.6	1.7	71	4A0	3.12	.09	.16	.48	10.0	.55	.93	11.60		.64	12.53	.75
FAGAG66	9439	103.6	104.9	1.3	92	4DEA4	3.52	.10	1.88	3.40	31.0	1.03	3.20	18.90		5.28	22.10	.64
FAGAG66	9440	104.9	106.2	1.3	100	4DEA4	3.59	.23	5.00	7.10	68.0	1.17	1.96	17.00		12.10	18.96	.59
FAGAG66	9441	107.2	107.8	.6	100	4AE	3.37	.14	.30	1.24	22.0	.55	1.86	18.70		1.54	20.56	.81
FAGAG66	9442	138.7	140.2	1.5	100	4A0	3.08	.05	.05	3.40	8.0	.07	5.50	6.20		3.45	11.70	.99
FAGAG66	9443	143.3	144.8	1.5	100	4A0		.07	.06	.38	6.0					.44		.86
FAGAG66	9444	155.4	156.4	1.0	90	4EA4	3.66	.13	7.20	9.70	128.0	1.71	1.60	16.70		16.90	18.30	.57
FAGAG66	9445	159.6	160.3	.7	86	4E#4	4.21	.27	5.30	6.80	101.0	2.12	1.76	29.00		12.10	30.76	.56
FAGAG66	9446	162.0	162.9	.9	100	4E1	4.11	.10	2.60	2.50	42.0	1.17	1.32	32.60		5.10	33.92	.49
FAGA121	9447	56.6	57.9	1.3	31	4A0	3.06	.08	.43	.86	15.0	.82	3.38	10.50		1.29	13.88	.67
FAGA121	9448	57.9	58.8	.9	33	4A0	3.09	.08	.30	.65	10.0	.62	1.81	10.40		.95	12.21	.68
FAGA121	9449	58.8	59.7	.9	89	4A3	3.39	.25	.45	.67	20.0	.89	.98	20.80		1.12	21.78	.60
FAGA121	9450	59.7	61.1	1.4	100	4E4	4.61	.21	12.40	20.90	143.0	1.10	1.52	21.50		33.30	23.02	.63
FAGA157	9451	74.6	76.6	2.0	80	4E4	4.45	.30	2.50	2.70	37.0	.82	2.64	33.20		5.20	35.84	.52
FAGA157	9452	76.6	78.0	1.4	100	4L0	3.15	.07	.69	.91	11.0	.21	3.15	5.90		1.60	9.05	.57
FAGA157	9453	104.6	105.8	1.2	58	4E1		.40	.93	.61	23.0					1.54		.40
FAGA157	9454	105.8	107.7	1.9	53	4E1		.35	.17	.28	15.0					.45		.62
FAGA157	9455	108.8	110.3	1.5	87	4A3		.27	.13	.19	12.0					.32		.59
FAGA157	9456	110.3	111.9	1.6	88	4A3		.13	.13	.17	12.0					.30		.57
FAGA157	9457	111.9	113.7	1.8	94	4A3		.13	.15	.16	12.0					.31		.52
FAGA157	9458	113.7	115.5	1.8	100	4A3		.40	.21	.44	17.0					.65		.68
FAGA157	9459	115.5	116.5	1.0	100	4A3		.42	.14	.21	15.0					.35		.60
FAGA157	9460	116.5	118.0	1.5	100	4C3		.37	.14	.22	16.0					.36		.61
FAGA157	9461	118.0	119.3	1.3	100	4C3	3.95	.17	1.82	3.50	40.0	.89	1.75	25.40		5.32	27.15	.66
FAGA157	9462	119.3	119.8	.5	100	4E4#	4.19	.20	7.60	7.20	100.0	.89	1.85	23.20		14.80	25.05	.49
FAGA157	9463	119.8	120.8	1.0	100	4E4#	4.89	.19	12.40	10.90	150.0	2.13	3.52	23.90		23.30	27.42	.47
FAGA157	9464	120.8	122.6	1.8	94	4C#	3.55	.35	1.61	1.26	30.0	.41	5.37	15.30		2.87	20.67	.44
FAGU141	9465	.0	2.2	2.2	50	4A0		.18	.59	1.94	26.0					2.53		.77
FAGU141	9466	2.2	4.5	2.3	96	4A0		.26	.37	1.58	25.0					1.95		.81
FAGU141	9467	4.5	5.7	1.2	100	4A0		.15	.58	.91	24.0					1.49		.61
FAGU141	9468	5.7	7.6	1.9	100	4A0	3.50	.14	.43	1.42	18.0	.62	1.79	18.90		1.85	20.69	.77
FAGU141	9469	7.6	9.2	1.6	94	4A4	3.60	.15	4.50	7.00	66.0	1.44	1.62	16.40		11.50	18.02	.61
FAGU141	9470	9.2	10.8	1.6	100	4E4	4.81	.15	7.40	12.70	103.0	3.29	2.33	28.20		20.10	30.53	.63
FAGU141	9471	10.8	12.5	1.7	100	4E4	4.65	.08	7.80	12.30	118.0	1.78	1.97	28.50		20.10	30.47	.61
FAGU141	9472	12.5	13.0	.5	100	4D0	4.07	.07	5.00	6.50	98.0	1.37	2.16	26.70		11.50	28.86	.57
FAGU141	9473	13.0	14.0	1.0	100	4E4	4.18	.05	7.00	13.70	96.0	1.37	2.27	21.10		20.70	23.37	.66
FAGU141	9474	14.0	14.4	.4	100	4G4	4.58	.17	3.70	7.90	68.0	1.78	.62	29.30		11.60	29.92	.68
FAGU141	9475	14.4	16.4	2.0	100	4D4	4.03	.12	8.30	12.90	130.0	1.92	2.46	18.50		21.20	20.96	.61
FAGU141	9476	16.4	17.6	1.2	100	4D34	3.58	.19	1.95	12.80	39.0	1.71	2.23	21.80		14.75	24.03	.87

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAO	PB+ZN	PC+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGU141	9477	17.6	18.5	.9	100	4A4	3.75	.12	7.30	6.40	95.0	2.33	1.40	18.40		13.70	19.80	.47
FAGU141	9478	18.5	19.9	1.4	100	4D4	3.80	.32	6.30	6.80	93.0	2.40	2.46	19.00		13.10	21.46	.52
FAGU141	9479	19.9	21.3	1.4	57	4D4	3.82	.17	6.10	4.60	98.0	2.19	1.58	20.40		10.70	21.98	.43
FAGU141	9480	21.3	22.4	1.1	100	4C3	4.39	.39	2.60	1.40	46.0	2.88	2.10	29.90		4.00	32.00	.35
FAGU141	9481	22.4	24.1	1.7	76	4D43	3.61	.21	7.60	10.70	125.0	1.99	3.06	12.80		18.30	15.86	.58
FAGU141	9482	59.8	61.5	1.7	100	4GE4	4.40	.17	5.20	8.40	93.0	.89	2.14	23.50		13.60	25.64	.62
FAGU141	9483	61.5	62.7	1.2	100	4G4	4.48	.05	4.00	8.20	76.0	.62	.51	8.50		12.20	9.01	.67
FAGU157	9484	.0	2.0	2.0	30	4A0	3.07	.11	.54	1.91	16.0	.21	.98	10.80		2.45	11.78	.78
FAGU157	9485	2.0	4.0	2.0	40	4A0	3.18	.12	.36	.76	13.0	.07	2.12	14.80		1.12	16.92	.68
FAGU157	9486	4.0	6.0	2.0	95	4A0	3.40	.16	.69	1.58	21.0	.96	2.08	20.30		2.27	22.38	.70
FAGU157	9487	6.0	7.3	1.3	100	4A0	3.38	.13	1.57	2.31	27.0	1.17	2.30	17.50		3.88	19.80	.60
FAGU157	9488	7.3	9.1	1.8	100	4A0	3.84	.17	1.34	1.39	29.0	2.88	1.84	24.30		2.73	26.14	.51
FAGU157	9489	9.1	10.6	1.5	100	4A0	3.39	.16	.53	1.44	18.0	1.10	2.59	17.70		1.97	20.29	.73
FAGU157	9490	10.6	12.0	1.4	100	4A0		.15	.10	.24	6.0					.34		.71
FAGU157	9491	12.0	13.7	1.7	76	4EA		.24	.11	1.58	15.0					1.69		.93
FAGU157	9492	13.7	15.7	2.0	85	4AG		.24	.11	.78	12.0					.89		.88
FAGU157	9493	15.7	17.7	2.0	100	4A0		.19	.09	.42	12.0					.51		.82
FAGU157	9494	17.7	19.7	2.0	70	4A4	3.01	.15	5.50	1.13	186.0	.21	1.12	6.40		6.63	7.52	.17
FAGU157	9495	19.7	21.7	2.0	80	4A0	3.08	.22	1.18	.22	40.0	.27	.81	10.40		1.40	11.21	.16
FAGU157	9496	21.7	23.2	1.5	100	4A0		.11	.26	.17	80.0					.43		.40
FAGU157	9497	23.2	24.7	1.5	100	4CA		.16	.22	.20	25.0					.42		.48
FAGU157	9498	24.7	26.1	1.4	100	4CA		.32	.14	.31	18.0					.45		.69
FAGU157	9499	26.1	28.1	2.0	100	4A0		.08	.04	1.52	7.0					1.56		.97
FAGU157	9500	28.1	29.4	1.3	100	4A0		.12	.04	.33	14.0					.37		.89
FAGA121	9501	61.1	63.2	2.1	100	4DE4	3.84	.10	8.40	14.41	129.0	1.23	1.52	16.30		22.81	17.82	.63
FAGA121	9502	63.2	64.8	1.6	100	4E4#	4.67	.17	7.10	12.18	120.0	.96	1.03	31.60		19.28	32.63	.63
FAGA121	9503	64.8	66.8	2.0	100	4A0	2.98	.12	.64	1.73	17.0	.69	.54	8.50		2.37	9.04	.73
FAGA121	9504	156.7	159.4	2.7	44	4A13		.06	1.83	3.00	36.0					4.83		.62
FAGA121	9505	159.4	160.4	1.0	80	5AD		.02	.49	1.05	13.0					1.54		.68
FAGA121	9506	180.4	181.0	.6	83	4G4#	3.91	.05	6.60	8.00	85.0	.55	2.15	15.30		14.60	17.45	.55
FAGA121	9507	181.0	183.1	2.1	100	4E8	4.51	.35	.62	.58	18.0	.96	5.50	36.60		1.20	42.10	.48
FAGA121	9508	183.1	185.2	2.1	100	4E8	4.56	.38	1.02	.91	21.0	1.51	7.90	34.70		1.93	42.60	.47
FAGA121	9509	185.2	187.2	2.0	100	4E8	4.02	.24	.75	1.16	20.0	1.17	6.10	28.90		1.91	35.00	.61
FAGA121	9510	187.2	188.4	1.2	100	4E#	4.13	.14	.38	.15	13.0	1.10	2.10	33.90		.53	36.00	.28
FAGA121	9511	188.4	189.7	1.3	92	4E#4	4.03	.11	3.40	4.80	54.0	1.30	2.03	27.00		8.20	29.03	.59
FAGA121	9512	189.7	191.7	2.0	100	4CE	3.83	.23	1.35	1.58	28.0	.96	7.80	20.90		2.93	28.70	.54
FAGA121	9513	191.7	193.7	2.0	80	4CE	3.61	.39	3.10	1.05	40.0	.82	7.90	20.30		4.15	28.20	.25
FAGA121	9514	193.7	195.7	2.0	100	4DE	3.45	.14	4.70	.56	12.0	.41	6.50	16.30		5.26	22.80	.11
FAGA121	9515	195.7	197.7	2.0	100	4DE	3.45	.18	9.70	1.00	19.0	.34	8.40	15.50		10.70	23.90	.09
FAGA121	9516	197.7	199.7	2.0	100	4CE	3.34	.18	.45	1.15	13.0	.55	4.40	15.30		1.60	19.70	.72
FAGA121	9517	199.7	201.7	2.0	100	4CE	3.47	.35	1.58	1.71	31.0	1.23	4.60	16.30		3.29	20.90	.52
FAGA121	9518	201.7	202.2	.5	100	4DE4	3.45	.10	7.10	7.20	98.0	1.03	4.10	12.90		14.30	17.00	.50
FAGA121	9519	202.2	203.6	1.4	100	4DE	3.18	.13	2.70	3.00	48.0	.96	2.31	9.40		5.70	11.71	.53
FAGA121	9520	203.6	205.5	1.9	53	4C3	3.69	.23	1.01	1.60	27.0	1.23	4.40	23.90		2.61	28.30	.61
FAGA121	9521	206.0	207.6	1.6	69	4C3	3.82	.43	1.83	1.69	43.0	1.65	4.60	24.50		3.52	29.10	.48
FAGA121	9522	207.6	208.2	.6	33	4C3	3.74	.64	.72	.68	32.0	.75	3.10	27.90		1.40	31.00	.49
FAGA121	9523	208.2	209.1	.9	44	4E4	3.56	.13	2.40	4.20	56.0	.62	8.30	16.50		6.60	24.80	.64
FAGU159	9524	19.7	21.7	2.0	100	4A0		.09	.24	.52	15.0					.76		.68
FAGU159	9525	21.7	23.7	2.0	45	4A0		.17	.08	1.05	20.0					1.13		.93
FAGU159	9526	23.7	25.7	2.0	85	4A0		.12	1.00	.22	41.0					1.22		.18

DDH	SAMPLE	---DEPTHS---	INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAC	PB+ZN	PO+PY	ZN
		FROM TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGU159	9527	25.7	27.7	2.0	80	4A0	3.10	.10	.34	.59	16.0	.69	.20	14.20	.93	14.40	.63
FAGU159	9528	27.7	29.0	1.3	38	4A4	3.59	.09	4.30	7.80	73.0	1.85	.88	14.10	12.10	14.98	.64
FAGU159	9529	29.0	30.5	1.5	73	4D4	3.53	.20	7.10	11.60	127.0	2.06	.94	15.00	18.70	15.94	.62
FAGU159	9530	30.5	30.9	.4	100	4E4	4.43	.19	8.00	16.10	139.0	1.85	3.59	24.70	24.10	28.29	.67
FAGU159	9531	30.9	32.0	1.1	64	4A0	3.14	.12	1.39	2.90	31.0	.89	2.79	12.60	4.29	15.39	.68
FAGU159	9532	52.3	54.3	2.0	100	4EA4	3.65	.09	5.10	7.30	77.0	1.71	5.13	17.70	12.40	22.83	.59
FAGU159	9533	54.3	56.3	2.0	95	4EA	3.68	.20	.92	3.20	26.0	1.58	2.27	26.60	4.12	28.87	.78
FAGU159	9534	56.3	57.9	1.6	94	4EA4	3.69	.19	2.80	2.80	59.0	1.78	1.20	26.40	5.60	27.60	.50
FAGU159	9535	57.9	60.0	2.1	100	4A13	3.36	.08	1.27	3.20	23.0	1.10	2.07	18.20	4.47	20.27	.72
FAGU159	9536	60.0	61.5	1.5	100	4EA4	3.85	.13	4.00	6.50	69.0	1.71	1.74	16.10	10.50	17.84	.62
FAGU159	9537	61.5	63.0	1.5	100	4A10	3.59	.08	1.35	3.50	23.0	1.51	1.62	24.50	4.85	26.12	.72
FAGU159	9538	63.0	64.0	1.0	50	4D0	3.58	.16	2.00	5.50	29.0	2.33	2.29	15.50	7.50	17.79	.73
FAGU159	9539	64.0	65.3	1.3	100	4A13	3.30	.11	.40	.79	10.0	1.37	.56	21.30	1.19	21.86	.66
FAGU159	9540	65.3	67.3	2.0	65	4EA	3.81	.18	.58	1.09	15.0	1.65	1.02	30.70	1.67	31.72	.65
FAGU159	9541	67.3	69.3	2.0	100	4EA4	3.51	.15	2.05	3.20	43.0	1.92	.80	23.30	5.25	24.10	.61
FAGU159	9542	69.3	71.1	1.8	83	4EA	3.62	.09	.70	2.90	18.0	1.37	1.68	28.70	3.60	30.38	.81
FAGU159	9543	71.1	73.2	2.1	100	4A14	2.87	.02	1.91	5.20	24.0	.62	1.29	3.82	7.11	5.11	.73
FAGU159	9544	73.2	74.7	1.5	53	4L14	2.84	.04	2.60	5.70	35.0	.75	.90	1.92	8.30	2.82	.69
FAGU159	9545	74.7	76.2	1.5	87	4L14	2.96	.06	3.30	8.30	52.0	.75	1.11	3.34	11.60	4.45	.72
FAGU161	9546	2.7	4.7	2.0	65	4A3		.07	.54	1.05	12.0				1.59		.66
FAGU161	9547	4.7	6.6	1.9	53	4A3		.15	.19	.83	10.0				1.02		.81
FAGU161	9548	6.6	8.5	1.9	100	4A3		.16	.12	.59	8.0				.71		.83
FAGU161	9549	8.5	10.4	1.9	100	4A3	3.05	.10	.35	.85	10.0	.55	2.05	15.40	1.20	17.45	.71
FAGU161	9550	10.4	12.3	1.9	100	4A3	3.31	.14	1.05	2.50	16.0	.96	1.76	18.40	3.55	20.16	.70
FAGU161	9551	12.3	13.7	1.4	100	4A34	3.37	.13	2.08	2.60	41.0	1.10	1.52	18.50	4.68	20.02	.56
FAGU161	9552	13.7	14.7	1.0	100	4E15	3.87	.26	1.53	1.86	30.0	2.19	1.42	28.70	3.39	30.12	.55
FAGU161	9553	14.7	15.7	1.0	100	4D45	3.47	.06	5.00	4.10	76.0	1.44	1.96	15.40	9.10	17.36	.45
FAGU161	9554	15.7	17.2	1.5	100	4D45	3.70	.08	5.70	8.30	80.0	1.37	2.35	15.50	14.00	17.85	.59
FAGU161	9555	17.2	19.0	1.8	100	4A34	3.60	.11	3.10	3.50	47.0	1.17	1.53	19.40	6.60	20.93	.53
FAGU161	9556	19.0	20.1	1.1	100	4A13	3.62	.23	2.70	1.11	47.0	1.37	1.81	21.40	3.81	23.21	.29
FAGU161	9557	20.1	21.8	1.7	100	4A4	3.39	.16	3.90	3.70	63.0	1.44	1.53	13.70	7.60	15.23	.49
FAGU161	9558	21.8	23.5	1.7	94	4A4	3.34	.10	6.40	11.60	106.0	1.71	2.10	9.10	18.00	11.20	.64
FAGU161	9559	23.5	23.9	.4	100	4D4	3.92	.14	7.30	16.20	113.0	2.81	1.39	14.70	23.50	16.09	.69
FAGU161	9560	23.9	25.2	1.3	100	4E#4	4.81	.19	6.40	11.60	114.0	1.85	1.19	29.20	18.00	30.39	.64
FAGU161	9561	25.2	26.6	1.4	100	4E#4	4.80	.06	6.20	10.40	124.0	1.17	.91	29.60	16.60	30.51	.63
FAGU161	9562	26.6	28.8	2.2	100	4A41	3.69	.10	7.20	9.70	123.0	1.37	1.86	10.20	16.90	12.06	.57
FAGU161	9563	28.8	31.0	2.2	100	4A41	3.68	.07	5.40	8.10	87.0	1.58	1.81	13.60	13.50	15.41	.60
FAGU161	9564	31.0	33.2	2.2	100	4D4	3.72	.06	6.50	9.80	104.0	1.58	2.40	10.90	16.30	13.30	.60
FAGU161	9565	33.2	33.6	.4	100	4E18	4.47	.06	2.90	2.40	44.0	1.51	3.64	29.40	5.30	33.04	.45
FAGU161	9566	33.6	35.2	1.6	94	4D0	4.06	.08	2.40	3.60	37.0	1.10	2.13	19.40	6.00	21.53	.60
FAGU161	9567	35.2	37.2	2.0	100	4A314	3.52	.09	2.80	3.40	43.0	1.23	1.48	13.50	6.20	14.98	.55
FAGU161	9568	37.2	39.2	2.0	100	4A314	3.41	.09	3.50	5.80	49.0	1.44	1.68	16.30	9.30	17.98	.62
FAGU161	9569	39.2	41.2	2.0	100	4A314	3.56	.10	2.60	3.70	29.0	1.10	1.29	13.30	6.30	14.59	.59
FAGU161	9570	41.2	43.0	1.8	100	4E145	4.01	.19	2.05	3.40	30.0	1.03	1.39	25.70	5.45	27.09	.62
FAGU161	9571	43.0	45.2	2.2	95	4CE	3.94	.33	.10	.87	10.0	.75	2.08	26.40	.97	28.48	.90
FAGU161	9572	45.2	47.1	1.9	100	4A13	3.36	.25	.14	.36	15.0	.96	1.91	20.10	.50	22.01	.72
FAGU161	9573	47.1	48.5	1.4	100	4CE	3.90	.32	.26	.96	16.0	1.03	1.77	23.60	1.22	25.37	.79
FAGU161	9574	48.5	49.9	1.4	100	4CE	3.94	.28	.50	1.08	17.0	1.23	2.63	23.70	1.58	26.33	.68
FAGU161	9575	49.9	51.6	1.7	94	4DE4	3.85	.15	5.20	3.90	86.0	2.40	1.67	18.80	9.10	20.47	.43
FAGU161	9576	51.6	53.3	1.7	82	4DE4	3.75	.15	4.20	4.50	64.0	1.71	2.04	17.90	8.70	19.94	.52

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAO	PB+ZN	PO+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGU161	9577	54.3	55.1	.8	100	4L4	3.21	.05	1.71	3.60	24.0	.34	2.82	3.30		5.31	6.12	.68
FAGU161	9578	55.1	56.1	1.0	70	4E14	3.68	.07	6.70	8.00	93.0	1.23	5.60	8.10		14.70	13.70	.54
FAGA121	9579	209.1	210.0	.9		4L0			.10	.10	2.1					.20		.50
FAGU054	9585	.0	2.0	2.0	75	4A4	3.45	.03	1.88	4.50	42.0	1.23	1.47	22.10		6.38	23.57	.71
FAGU054	9586	2.0	4.0	2.0	95	4A0	3.28	.02	1.50	3.10	33.0	1.03	.94	10.90		4.60	11.84	.67
FAGU054	9587	4.0	6.0	2.0	85	4A4	3.11	.04	1.71	3.60	39.0	.69	1.52	13.30		5.31	14.82	.68
FAGU054	9588	6.0	8.0	2.0	80	4A4	3.27	.04	1.57	3.50	37.0	.82	1.04	17.80		5.07	18.84	.69
FAGU054	9589	8.0	10.0	2.0	100	4A4	3.29	.03	2.90	6.70	56.0	.89	1.44	14.10		9.60	15.54	.70
FAGU054	9590	10.0	12.0	2.0	100	4A4	3.48	.10	2.40	4.50	52.0	1.10	1.69	19.20		6.90	20.89	.65
FAGU054	9591	12.0	15.2	3.2	66	4A4	2.90	.04	2.20	3.60	29.0	.82	1.48	5.60		5.80	7.08	.62
FAGU054	9592	15.2	16.8	1.6	100	4A0	3.18	.05	1.67	3.00	33.0	.75	.68	14.70		4.67	15.38	.64
FAGU054	9593	16.8	18.2	1.4	100	4A0	3.40	.08	1.02	1.62	25.0	1.10	.67	17.50		2.64	18.17	.61
FAGU054	9594	18.2	19.8	1.6	100	4A4	3.31	.04	2.40	6.50	44.0	.96	1.40	12.50		8.90	13.90	.73
FAGU054	9595	19.8	21.3	1.5	100	4A4	3.39	.05	2.90	4.80	45.0	.89	1.21	15.20		7.70	16.41	.62
FAGU054	9596	21.3	23.3	2.0	95	4A4	3.48	.03	3.90	8.60	62.0	1.03	1.30	12.30		12.50	13.60	.69
FAGU054	9597	23.3	25.3	2.0	100	4A4	3.31	.03	4.50	9.00	73.0	.96	1.89	8.20		13.50	10.09	.67
FAGU054	9598	25.3	27.3	2.0	90	4A4	3.16	.04	3.20	8.00	55.0	.82	1.79	7.10		11.20	8.89	.71
FAGU054	9599	27.3	29.3	2.0	100	4A4	3.25	.13	3.90	9.40	69.0	1.30	1.49	9.40		13.30	10.89	.71
FAGU054	9600	29.3	30.9	1.6	100	4A4	3.49	.19	6.90	13.20	116.0	1.51	1.93	11.20		20.10	13.13	.66
FAGU054	9601	30.9	32.5	1.6	94	4A4	3.41	.05	6.20	13.50	106.0	1.23	1.44	8.70		19.70	10.14	.69
FAGU054	9602	32.5	33.9	1.4	100	4A4	3.28	.06	5.40	10.00	85.0	1.23	1.14	8.90		15.40	10.04	.65
FAGU054	9603	33.9	34.9	1.0	90	4D0	3.01	.02	3.60	8.60	61.0	.62	.90	4.61		12.20	5.51	.70
FAGU054	9604	34.9	35.6	.7	100	4A4	3.41	.06	8.30	16.70	141.0	.89	2.19	7.90		25.00	10.09	.67
FAGU054	9605	35.6	37.2	1.6	100	4D0	3.07	.04	3.20	7.30	58.0	.82	2.60	6.70		10.50	9.30	.70
FAGU054	9606	40.0	42.0	2.0	60	4A4	3.39	.08	3.20	5.20	52.0	1.78	1.61	12.30		8.40	13.91	.62
FAGU054	9607	42.0	44.3	2.3	65	4C0	3.03	.10	.34	1.61	10.0	.89	2.50	9.70		1.95	12.20	.83
FAGU054	9608	44.3	45.9	1.6	100	4C0	2.99	.11	1.07	1.44	17.0	1.30	.88	9.30		2.51	10.18	.57
FAGU054	9609	45.9	47.2	1.3	62	4AE	3.38	.20	.82	1.25	18.0	1.78	.99	20.50		2.07	21.49	.60
FAGU054	9610	47.2	51.3	4.1	39	4AE	3.49	.22	1.65	3.10	26.0	1.44	1.04	21.90		4.75	22.94	.65
FAGU054	9611	51.3	53.3	2.0	100	4A4	3.14	.04	3.40	7.90	48.0	.82	1.67	8.40		11.30	10.07	.70
FAGU054	9612	53.3	55.4	2.1	100	4A4	3.34	.05	2.80	5.10	46.0	.82	1.92	10.40		7.90	12.32	.65
FAGU054	9613	55.4	56.1	.7	86	5D4*	3.01	.06	3.30	8.90	52.0	.27	8.46	1.89		12.20	10.35	.73
FAGU054	9614	56.1	57.9	1.8	100	4A14	2.99	.03	3.20	5.00	54.0	.55	1.69	2.73		8.20	4.42	.61
FAGU054	9615	57.9	59.9	2.0	35	4A14	2.87	.03	2.70	3.50	40.0	.48	1.36	1.40		6.20	2.76	.56
FAGU054	9616	59.9	61.9	2.0	100	4A1	3.07	.05	1.93	1.21	24.0	1.51	2.31	5.70		3.14	8.01	.39
FAGU054	9617	61.9	62.5	.6	100	4A1	2.99	.07	1.34	1.31	20.0	1.03	1.86	6.80		2.65	8.66	.49
FAGU054	9618	62.5	63.4	.9	89	4L12	2.96	.03	1.75	2.60	21.0	.55	2.02	3.83		4.35	5.85	.60
FAGU054	9619	63.4	65.4	2.0	100	4A14	3.13	.02	2.80	5.40	39.0	.69	1.76	7.03		8.20	8.79	.66
FAGU054	9620	65.4	67.1	1.7	100	4A14	2.96	.01	3.50	6.10	44.0	1.37	1.58	5.80		9.60	7.38	.64
FAGU054	9621	67.1	68.7	1.6	100	4A14	2.93	.02	2.30	5.40	33.0	.62	1.76	4.17		7.70	5.93	.70
FAGU054	9622	69.6	70.2	.6	100	4D0	3.06	.05	2.40	4.70	31.0	.55	3.91	6.13		7.10	10.04	.66
FAGU054	9623	70.2	70.5	.3	100	5C4*	2.99	.01	.22	5.60	3.0	.27	10.40	1.26		5.82	11.66	.96
FAGU054	9624	70.5	71.2	.7	100	4AE4	3.70	.14	4.50	6.90	77.0	1.58	2.20	14.10		11.40	16.30	.61
FAGU054	9625	94.0	94.7	.7	100	4A14	3.25	.07	2.90	7.00	56.0	.48	4.89	7.30		9.90	12.19	.71
FAGU054	9626	94.7	96.7	2.0	90	4L124	3.05	.04	1.68	2.20	27.0	.75	4.07	5.50		3.88	9.57	.57
FAGU054	9627	96.7	98.7	2.0	100	4L124	3.10	.04	2.30	4.80	46.0	.89	3.83	5.70		7.10	9.53	.68
FAGU054	9628	98.7	100.6	1.9	100	4L124	2.95	.05	1.76	3.40	29.0	.89	3.09	4.06		5.16	7.15	.66
FAGU054	9629	100.6	101.8	1.2	100	4L124	2.93	.05	2.20	3.70	40.0	.55	3.05	6.10		5.90	9.15	.63
FAGU054	9630	101.8	103.3	1.5	100	4A14	3.12	.03	3.20	9.70	77.0	.48	5.33	3.30		12.90	8.63	.75

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAC	PB+ZN	PG+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGU054	9631	103.3	104.8	1.5	100	4A14	3.41	.02	3.60	8.00	82.0	.41	6.45	6.00		11.60	12.45	.69
FAGU054	9632	104.8	106.6	1.8	100	400	3.14	.02	3.80	10.00	84.0	.41	5.97	3.68		13.80	9.65	.72
FAGU054	9633	106.6	107.3	.7	100	5DC4*	3.14	.01	.56	5.90	14.0	.21	13.12	2.02		6.46	15.14	.91
FAGU054	9634	107.3	109.1	1.8	100	4A0	3.10	.03	.55	1.88	10.0	.27	9.08	5.10		2.43	14.18	.77
FAGU054	9635	115.2	116.3	1.1	100	480	3.01	.03	1.85	8.10	35.0	.27	5.87	5.50		9.95	11.37	.81
FAGU054	9636	116.3	117.0	.7	100	5D6	3.80	.04	1.37	2.80	20.0	.34	13.20	16.50		4.17	29.70	.67
FAGU145	9637	2.3	4.1	1.8	78	4A0		.19	.10	.94	8.0					1.04		.90
FAGU145	9638	4.1	5.9	1.8	100	4A0		.12	.03	1.25	6.0					1.28		.98
FAGU145	9639	5.9	7.7	1.8	100	4A0		.18	.09	.53	8.0					.62		.85
FAGU145	9640	7.7	9.5	1.8	100	4A0		.10	.30	1.08	13.0					1.38		.78
FAGU145	9641	9.5	10.0	.5	100	4A0		.16	.09	1.45	7.0					1.54		.94
FAGU145	9642	10.0	12.1	2.1	100	4A0		.21	.15	.69	11.0					.84		.82
FAGU145	9643	12.1	14.2	2.1	100	4A0		.40	.25	.60	21.0					.85		.71
FAGU145	9644	14.2	16.3	2.1	100	4A0		.20	.06	.42	6.0					.48		.88
FAGU145	9645	16.3	18.5	2.2	100	4A0		.11	.06	.44	5.0					.50		.88
FAGU145	9646	18.5	20.7	2.2	100	4A0		.14	.23	.84	10.0					1.07		.79
FAGU145	9647	20.7	22.9	2.2	100	4A0		.20	.04	.33	6.0					.37		.89
FAGU145	9648	22.9	24.9	2.0	100	4A0		.10	.04	.40	6.0					.44		.91
FAGU145	9649	24.9	26.9	2.0	100	4A0		.07	.03	.26	3.0					.29		.90
FAGU145	9650	26.9	28.9	2.0	100	4A0		.09	.03	.33	4.0					.36		.92
FAGU145	9651	28.9	30.9	2.0	100	4A0		.09	.04	.39	6.0					.43		.91
FAGU145	9652	30.9	33.0	2.1	100	4A0		.10	.08	.24	7.0					.32		.75
FAGU145	9653	33.0	35.1	2.1	90	4A0		.09	.04	.28	6.0					.32		.87
FAGU145	9654	38.5	40.4	1.9	95	4A0		.12	.05	.29	7.0					.34		.85
FAGU145	9655	40.4	42.3	1.9	100	4A0		.13	.05	.33	6.0					.38		.87
FAGU145	9656	42.3	44.2	1.9	100	4A0		.22	.04	.30	8.0					.34		.88
FAGU145	9657	44.2	46.1	1.9	74	4A0	3.21	.28	.03	.75	10.0	.41	2.70	12.00		.78	14.70	.96
FAGU145	9658	46.1	48.1	2.0	100	4A0	3.89	.19	1.21	3.30	28.0	.89	2.31	23.60		4.51	25.91	.73
FAGU145	9659	48.1	49.9	1.8	100	4EA	4.57	.27	1.65	3.70	35.0	1.10	2.31	32.50		5.35	34.81	.69
FAGU145	9660	49.9	51.6	1.7	100	4A4	3.66	.04	2.50	3.20	45.0	.82	1.99	16.60		5.70	18.59	.56
FAGU145	9661	88.6	90.6	2.0	100	5A69	2.98	.02	.32	.60	8.0	.27	1.99	3.35		.92	5.34	.65
FAGU145	9662	90.6	92.8	2.2	100	4A4	3.08	.03	2.60	4.60	43.0	.55	1.67	7.20		7.20	8.87	.64
FAGU145	9663	92.8	93.2	.4	75	4G4	4.07	.03	4.30	7.30	69.0	.48	.91	9.70		11.60	10.61	.63
FAGU145	9664	93.2	94.5	1.3	100	4A4	3.12	.03	2.60	4.00	51.0	.55	1.10	7.10		6.60	8.20	.61
FAGU145	9665	97.7	98.7	1.0	90	4LG	3.20	.06	1.47	2.50	28.0	.41	2.40	6.80		3.97	9.20	.63
FAGU145	9666	98.7	99.3	.6	100	4A0	3.33	.03	.71	1.32	19.0	.34	2.96	14.50		2.03	17.46	.65
FAGU145	9667	99.3	100.7	1.4	100	4E8	4.26	.23	1.87	1.95	32.0	.75	5.20	30.30		3.82	35.50	.51
FAGU145	9668	100.7	102.0	1.3	92	4E8	4.10	.20	2.04	1.00	31.0	1.23	7.10	27.00		3.04	34.10	.33
FAGU145	9669	102.0	104.1	2.1	100	4CE8	3.82	.27	1.40	2.80	32.0	.62	4.83	20.70		4.20	25.53	.67
FAGU145	9670	104.1	105.4	1.3	100	4LC	3.11	.09	.40	.26	14.0	.34	2.95	5.10		.66	8.05	.39
FAGU145	9671	105.4	106.0	.6	100	4E4	3.17	.31	1.97	3.60	44.0	1.37	4.20	24.70		5.57	28.90	.65
FAGU145	9672	106.0	106.7	.7	86	4G4#	3.89	.11	3.90	8.40	70.0	.89	2.18	10.20		12.30	12.38	.68
FAGU143	9673	.0	2.0	2.0	15	4A0		.04	.23	.27	4.0					.50		.54
FAGU143	9674	2.0	4.0	2.0	90	4A0		.10	.14	.53	5.0					.67		.79
FAGU143	9675	4.0	6.0	2.0	85	4A0		.12	.12	.54	6.0					.66		.82
FAGU143	9676	6.0	8.0	2.0	100	4A0		.12	.12	.30	5.0					.42		.71
FAGU143	9677	8.0	10.0	2.0	100	4A0		.21	.16	.49	8.0					.65		.75
FAGU143	9678	10.0	12.0	2.0	100	4A0		.12	.07	.22	4.0					.29		.76
FAGU143	9679	12.0	14.0	2.0	100	4A0		.15	.05	.15	4.0					.20		.75
FAGU143	9680	14.0	16.0	2.0	100	4A0		.47	.10	.33	52.0					.43		.77

DDH	SAMPLE	---DEPTHS---	INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAO	PB+ZN	PO+PY	ZN
		FROM TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGU143	9681	16.0	18.0	2.0	100	4A0	.48	.08	.16	14.0					.24		.67
FAGU143	9682	18.0	20.0	2.0	100	4A0	.11	.18	.53	7.0					.71		.75
FAGU143	9683	20.0	22.0	2.0	95	4A0	.15	.22	.77	8.0					.99		.78
FAGU143	9684	22.0	24.0	2.0	100	4A0	.32	.23	.18	11.0					.41		.44
FAGU143	9685	24.0	26.0	2.0	100	4A0	.10	.14	.13	6.0					.27		.48
FAGU143	9686	26.0	28.0	2.0	100	4A0	.05	.04	.24	4.0					.28		.86
FAGU143	9687	28.0	30.0	2.0	100	4A0	.04	.52	.51	14.0					1.03		.50
FAGU143	9688	30.0	32.0	2.0	100	4A0	.06	.14	.31	5.0					.45		.69
FAGU143	9689	32.0	34.0	2.0	100	4A0	.07	.08	.35	4.0					.43		.81
FAGU143	9690	34.0	36.0	2.0	100	4A0	.08	.34	.49	11.0					.83		.59
FAGU143	9691	36.0	38.0	2.0	100	4A0	.08	.04	.27	6.0					.31		.87
FAGU143	9692	38.0	40.0	2.0	100	4A0	.04	.22	.91	8.0					1.13		.81
FAGU143	9693	40.0	42.7	2.7	74	4A0	.06	.06	.62	4.0					.68		.91
FAGU143	9694	58.0	60.4	2.4	46	4A0	.06	.13	.12	3.0					.25		.48
FAGU143	9695	60.4	62.8	2.4	67	4A0	.10	.03	.16	3.0					.19		.84
FAGU143	9696	64.0	66.0	2.0	100	4A0	.08	.07	.67	6.0					.74		.91
FAGU143	9697	66.0	68.0	2.0	100	4A0	.14	.02	.36	3.0					.38		.95
FAGU143	9698	68.0	70.0	2.0	60	4A0	.10	.01	.13	2.0					.14		.93
FAGU143	9699	72.0	74.0	2.0	100	4A0	.11	.01	.04	3.0					.05		.80
FAGU143	9700	74.0	76.0	2.0	100	4A0	.08	.03	.09	2.0					.12		.75
FAGU157	9701	29.4	30.9	1.5	100	4A0	.28	.15	.63	13.0					.78		.81
FAGU157	9702	30.9	32.4	1.5	100	4C0	.16	.11	.45	7.0					.56		.80
FAGU157	9703	32.4	33.9	1.5	100	4A9	.26	.03	1.34	5.0					1.37		.98
FAGU157	9704	33.9	35.5	1.6	100	4A9	.19	.03	.27	4.0					.30		.90
FAGU157	9705	35.5	37.3	1.8	100	4C0	.31	.03	.07	6.0					.10		.70
FAGU157	9706	37.3	39.3	2.0	100	4A0	.15	.04	.32	4.0					.36		.89
FAGU157	9707	39.3	40.3	1.0	100	4A0	.14	.05	.23	5.0					.28		.82
FAGU157	9708	40.3	42.7	2.4	71	4A0	.09	.09	.37	5.0					.46		.80
FAGU157	9709	42.7	44.7	2.0	85	4AE	3.74	.25	.65	1.98	22.0	.30	1.76	28.20	2.63	29.96	.75
FAGU157	9710	44.7	46.2	1.5	100	4AE	4.23	.42	1.41	2.93	37.0	1.37	1.66	32.60	4.34	34.26	.68
FAGU157	9711	121.2	121.8	.6	83	4D0	3.65	.23	2.70	3.15	93.0	.82	10.09	8.80	5.85	18.89	.54
FAGU157	9712	121.8	123.2	1.4	100	4G4*	4.28	.09	6.00	9.98	120.0	1.10	1.88	5.10	15.98	6.98	.62
FAGU157	9713	123.2	124.6	1.4	100	4G4*	4.25	.23	6.30	9.44	113.0	1.85	1.86	9.10	15.74	10.96	.60
FAGU157	9714	124.6	126.3	1.7	100	4E178	4.15	.34	3.20	2.06	50.0	1.03	11.78	22.30	5.26	34.08	.39
FAGU157	9715	126.3	127.0	.7	100	4E178	4.03	.29	3.50	3.90	57.0	1.71	4.94	25.20	7.40	30.14	.53
FAGU157	9716	129.4	131.0	1.6	50	4A0	.15	.49	.77	15.0					1.26		.61
FAGU155	9718	2.1	4.2	2.1	57	4A3	.09	.14	.61	6.0					.75		.81
FAGU155	9719	4.2	6.3	2.1	100	4A3	.14	.11	.49	11.0					.60		.82
FAGU155	9720	6.3	8.4	2.1	100	4A3	3.36	.21	.57	1.39	21.0	.55	2.42	17.50	1.96	19.92	.71
FAGU155	9721	8.4	10.4	2.0	100	4A3	3.37	.19	.90	1.77	20.0	.75	2.44	16.50	2.67	18.94	.66
FAGU155	9722	10.4	12.5	2.1	100	4A1	3.46	.14	.87	1.45	20.0	.75	2.14	19.00	2.32	21.14	.65
FAGU155	9723	12.5	14.5	2.0	100	4A1	3.54	.18	.43	1.04	15.0	.82	1.69	21.90	1.47	23.37	.71
FAGU155	9724	14.5	16.5	2.0	95	4A1	.20	.14	.70	8.0					.84		.65
FAGU155	9725	16.5	18.5	2.0	100	4A1	.23	.15	.63	10.0					.78		.61
FAGU155	9726	18.5	20.5	2.0	100	4A1	.19	.09	.90	7.0					.99		.91
FAGU155	9727	20.5	22.5	2.0	100	4A1	.14	.05	.35	5.0					.40		.88
FAGU155	9728	22.5	24.5	2.0	90	4A1	.22	.08	.50	7.0					.58		.86
FAGU155	9729	24.5	26.5	2.0	100	4A1	.26	.19	.58	10.0					.77		.75
FAGU155	9730	26.5	27.2	.7	100	4C0	.16	.43	1.29	11.0					1.72		.75
FAGU155	9731	27.2	27.8	.6	100	4A31	.09	.62	1.17	13.0					1.79		.65

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAO	PB+ZN	PC+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGU155	9732	27.8	30.4	2.6	100	4CA		.32	.19	.68	9.0					.87		.78
FAGU155	9733	30.4	31.8	1.4	86	4CA		1.00	.05	.50	14.0					.55		.91
FAGU155	9734	31.8	32.5	.7	100	4A31		.50	.04	.43	10.0					.47		.91
FAGU155	9735	32.5	34.5	2.0	100	4CAE		.56	.05	.93	16.0					.98		.95
FAGU155	9736	34.5	36.5	2.0	100	4CAE	3.39	.42	.06	1.14	12.0	.14	5.10	17.40		1.20	22.50	.95
FAGU155	9737	36.5	37.5	1.0	100	4CAE	3.88	.35	.26	2.97	18.0	.21	6.10	26.40		3.23	32.50	.92
FAGU155	9738	37.5	39.0	1.5	100	4CAE	3.38	.55	.13	1.27	16.0	.41	5.10	16.80		1.40	21.90	.91
FAGU155	9739	39.0	41.0	2.0	95	4C8	4.23	.31	.14	1.47	18.0	.14	11.40	28.50		1.61	39.90	.91
FAGU155	9740	41.0	43.0	2.0	100	4C8	3.81	.25	.53	1.77	26.0	.21	8.10	24.10		2.30	32.20	.77
FAGU155	9741	43.0	45.0	2.0	100	4C98	3.57	.65	.20	1.05	22.0	.55	5.40	22.40		1.25	27.80	.84
FAGU155	9742	45.0	47.3	2.3	100	4C98	3.78	.55	.18	1.59	21.0	.48	4.20	27.10		1.77	31.30	.90
FAGU155	9743	47.3	49.6	2.3	100	4C98	3.69	.24	.21	.51	15.0	1.23	2.10	28.60		.72	30.70	.71
FAGU155	9744	49.6	51.0	1.4	100	4DA4	3.61	.18	5.59	8.37	96.0	1.09	2.72	16.10		13.96	18.82	.60
FAGU155	9745	51.0	53.0	2.0	80	4E0		.33	.52	.96	26.0					1.48		.65
FAGA096	9746	49.4	53.1	3.7	54	4A0	2.95	.05	1.08	2.44	22.0	.82	1.38	5.75		3.52	7.13	.69
FAGA096	9747	53.1	56.6	3.5	49	4L42	3.11	.05	2.92	3.70	47.0	1.10	2.94	6.80		6.62	9.74	.56
FAGA096	9748	56.6	57.9	1.3	100	4A4	3.25	.09	3.12	5.70	49.0	1.37	2.27	9.30		8.82	11.57	.65
FAGA096	9749	57.9	59.7	1.8	83	4D0	3.34	.02	.92	6.90	19.0	.55	6.69	9.10		7.82	15.79	.88
FAGA096	9750	59.7	61.5	1.8	100	4A4	3.21	.02	2.20	5.80	47.0	.62	2.65	12.00		8.00	14.65	.73
FAGU143	9751	76.8	78.9	2.1	95	4AEL	3.34	.12	.81	1.45	24.0	1.17	2.03	16.10		2.26	18.13	.64
FAGU143	9752	78.9	80.0	1.1	82	4EAL	2.95	.17	2.29	2.97	64.0	1.51	1.84	21.80		5.26	23.64	.56
FAGU143	9753	80.0	82.3	2.3	87	4AE	3.00	.02	.52	1.18	11.0	3.57	3.31	5.20		1.70	8.51	.69
FAGU143	9754	83.3	85.3	2.0	100	4G0#	4.61	.16	5.68	4.20	64.0	3.02	1.39	19.90		9.88	21.29	.43
FAGU143	9755	85.3	87.3	2.0	100	4G0#	4.56	.17	5.59	4.20	67.0	2.47	2.62	28.40		9.79	31.02	.43
FAGU143	9756	87.3	88.4	1.1	100	4G0#	4.51	.14	3.60	3.60	54.0	1.85	1.84	24.90		7.20	26.74	.50
FAGU143	9757	88.4	90.4	2.0	100	4E8	4.70	.24	.51	.92	15.0	1.65	3.22	38.00		1.43	41.22	.64
FAGU143	9758	90.4	92.4	2.0	100	4E8	4.58	.48	.62	.87	21.0	2.33	6.23	35.60		1.49	41.83	.58
FAGU143	9759	92.4	94.4	2.0	95	4E84	4.15	.26	2.16	3.30	37.0	2.40	6.91	27.40		5.46	34.31	.60
FAGU143	9760	94.4	96.4	2.0	100	4E8	4.20	.27	1.87	1.38	34.0	1.30	5.94	31.00		3.25	36.94	.42
FAGU143	9761	96.4	98.5	2.1	100	4E8	4.10	.22	2.21	1.50	35.0	1.78	3.97	28.20		3.71	32.17	.40
FAGU143	9762	98.5	100.2	1.7	100	4E4	3.64	.11	4.60	8.70	86.0	.89	3.74	12.50		13.30	16.24	.65
FAGU143	9763	100.2	102.7	2.5	100	4ED	3.84	.16	2.13	4.90	46.0	1.23	5.49	19.70		7.03	25.19	.70
FAGU143	9764	102.7	104.7	2.0	100	4C879	3.68	.33	.46	.55	13.0	1.99	13.12	18.30		1.01	31.42	.54
FAGU143	9765	104.7	106.7	2.0	100	4C879		.47	.41	.56	16.0					.97		.58
FAGU143	9766	106.7	108.7	2.0	100	4C879		.44	.42	.67	15.0					1.09		.61
FAGU143	9767	108.7	110.7	2.0	100	4C879		.30	.71	1.00	20.0					1.71		.58
FAGU143	9768	110.7	112.7	2.0	95	4C879		.23	.47	.21	14.0					.68		.31
FAGU143	9769	112.7	114.7	2.0	100	4C79		.32	.43	.78	8.0					1.21		.64
FAGU143	9770	114.7	116.7	2.0	100	4C79		.47	.83	.64	18.0					1.47		.44
FAGU143	9771	116.7	118.7	2.0	100	4C79		.39	.38	.48	11.0					.86		.56
FAGU143	9772	118.7	120.7	2.0	100	4C79		.18	.27	.69	7.0					.96		.72
FAGU143	9773	120.7	121.8	1.1	100	4C79		.30	.18	.55	6.0					.73		.75
FAGU143	9774	121.8	123.8	2.0	100	4L24		.17	.18	.30	5.0					.48		.63
FAGU143	9775	123.8	125.8	2.0	95	4L24		.06	.28	.44	3.0					.72		.61
FAGU143	9776	125.8	128.0	2.2	95	4L24		.03	.32	1.00	4.0					1.32		.76
FAGA103	9777	136.8	138.8	2.0	100	4A0		.11	.23	.73	7.0					.96		.76
FAGA103	9778	138.8	140.8	2.0	90	4A0		.10	.07	.15	3.0					.22		.68
FAGA103	9779	140.8	142.8	2.0	95	4A0	2.98	.04	.21	.71	5.0	.55	3.43	4.89		.92	8.32	.77
FAGA103	9780	142.8	144.6	1.8	89	4A4	2.86	.03	2.93	4.30	36.0	.89	1.79	2.53		7.23	4.32	.59
FAGA103	9781	144.6	145.1	.5	100	4KAS	3.48	.09	2.93	4.10	47.0	.69	4.07	16.50		7.03	20.57	.58

DDH	SAMPLE	---DEPTHS---	INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	FY	BAO	PB+ZN	PC+PY	ZN
		FROM TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGA103	9782	147.0	148.6	1.6		4A0	2.98	.05	1.06	2.20	22.0	.55	2.94	4.60	3.26	7.54	.67
FAGA103	9783	160.0	160.9	.9	100	4E4#	4.29	.12	4.80	5.90	62.0	1.51	4.31	26.86	10.70	31.17	.55
FAGA103	9784	160.9	162.0	1.1	100	5D4S	2.92	.03	.21	.20	3.0	.27	5.36	1.30	.41	6.66	.49
FAGA103	9785	162.0	162.8	.8	100	4E#6	4.67	.02	3.60	5.00	35.0	.75	.82	35.60	8.60	36.42	.58
FAGA103	9786	162.8	163.8	1.0	90	4G4#	4.50	.03	2.61	5.70	28.0	.75	1.70	25.90	8.31	27.60	.69
FAGA103	9787	170.3	171.9	1.6	69	4G4#	3.92	.04	5.30	7.00	83.0	1.10	1.33	8.45	12.30	9.78	.57
FAGA102	9788	137.0	139.4	2.4	100	4A0	3.01	.04	1.40	2.10	23.0	.69	2.57	5.94	3.50	8.51	.60
FAGA102	9789	139.4	140.5	1.1	100	4E4	4.23	.13	8.40	8.10	106.0	1.65	5.88	22.10	16.50	27.98	.49
FAGA102	9790	140.5	142.0	1.5	100	4E0	4.14	.39	.96	1.25	25.0	1.30	2.20	33.30	2.21	35.50	.57
FAGA062	9793	48.2	52.1	3.9	18	4A0		.03	.49	.32	11.0				.81		.40
FAGA062	9794	74.4	76.5	2.1	33	4E4	3.60	.32	5.11	4.70	72.0	.69	6.31	14.50	9.81	20.81	.48
FAGA062	9795	81.8	83.3	1.5	100	4E4	4.67	.14	8.50	7.10	122.0	1.37	2.65	24.90	15.60	27.55	.46
FAGA062	9796	83.3	84.4	1.1	100	4E4	4.30	.12	9.90	5.50	124.0	.41	6.74	22.40	15.40	29.14	.36
FAGAG62	9797	84.4	85.6	1.2	92	4L2	2.98	.09	.70	.88	15.0	1.71	5.25	2.48	1.58	7.73	.56
FAGA062	9798	127.0	128.0	1.0	100	4E42	3.90	.07	6.40	11.80	113.0	1.17	6.31	15.70	18.20	22.01	.65
FAGA062	9799	128.0	130.1	2.1	100	4E42	4.37	.23	5.70	11.50	100.0	5.34	3.46	25.70	17.20	29.16	.67
FAGAG62	9800	130.1	131.8	1.7	94	4AE	2.95	.03	.64	1.35	13.0	2.95	1.45	7.30	1.99	8.75	.68
FAGA062	9801	131.8	133.0	1.2	83	4EL	2.93	.03	1.86	4.60	46.0	1.37	2.71	20.00	6.46	22.71	.71
FAGA062	9802	133.0	134.5	1.5	100	4GE	4.57	.11	4.30	8.30	93.0	1.23	1.08	13.10	12.60	14.18	.66
FAGA062	9803	134.5	135.9	1.4	86	4GE	4.66	.10	5.10	10.30	95.0	.75	2.31	22.10	15.40	24.41	.67
FAGA062	9804	135.9	137.2	1.3	92	4E4	4.69	.17	5.00	9.20	99.0	1.10	2.17	24.70	14.20	26.87	.65
FAGA062	9805	137.2	138.5	1.3	100	4E4	4.64	.18	5.20	11.70	106.0	2.26	2.61	26.40	16.90	29.01	.69
FAGAG62	9806	176.0	177.6	1.6	94	4A4	3.41	.12	3.00	5.50	50.0	.75	1.68	15.90	8.50	17.58	.65
FAGA062	9807	177.6	179.9	2.3	100	4EA	3.42	.35	.28	.75	17.0	.34	2.25	19.50	1.03	21.75	.73
FAGA062	9808	179.9	181.8	1.9	95	4A0	3.18	.22	.29	.58	10.0	.34	2.05	14.30	.87	16.35	.67
FAGA062	9809	181.8	183.6	1.8	67	4A0	3.38	.31	.14	.56	20.0	.21	1.99	19.30	.70	21.29	.80
FAGA062	9810	183.6	185.0	1.4	100	4EC	3.27	.48	.23	1.51	19.0	.34	2.98	16.00	1.74	18.98	.87
FAGA062	9811	185.0	186.4	1.4	86	4AE	3.50	.19	.36	1.50	18.0	.75	2.70	20.40	1.86	23.10	.81
FAGA062	9812	198.6	201.2	2.6	100	4L0		.07	.53	.76	10.0				1.29		.59
FAGAG62	9813	218.5	220.5	2.0	100	4L24		.14	1.19	1.35	16.0				2.54		.53
FAGAG62	9814	245.2	245.9	.7	86	4EL	2.97	.12	7.20	8.50	61.0	1.65	11.37	11.30	15.70	22.67	.54
FAGA062	9815	245.9	248.7	2.8	39	4ACL	2.87	.04	.22	.30	3.0	.01	2.97	3.00	.52	5.97	.58
FAGA062	9816	248.7	250.6	1.9	100	4L24	2.92	.04	.13	.20	2.0	.01	7.41	2.59	.33	10.00	.61
FAGA062	9817	250.6	252.7	2.1	95	4L24	2.95	.06	.09	.11	4.0	.01	5.44	4.28	.20	9.72	.55
FAGA062	9818	252.7	254.8	2.1	100	4E48	3.25	.23	3.00	3.80	48.0	1.58	6.14	27.10	6.80	33.24	.56
FAGA062	9819	254.8	256.6	1.8	100	4E80	4.49	.27	.90	1.37	19.0	1.99	6.76	35.00	2.27	41.76	.60
FAGA062	9820	256.6	258.5	1.9	95	4E80	4.40	.22	1.83	.98	37.0	2.19	5.28	34.60	2.81	39.88	.35
FAGA062	9821	258.5	260.3	1.8	100	4E48	4.29	.21	5.21	4.90	77.0	.34	9.26	23.20	10.11	32.46	.48
FAGA062	9822	260.3	262.1	1.8	100	4E48	4.26	.32	2.70	3.00	44.0	2.61	7.23	27.30	5.70	34.53	.53
FAGA062	9823	267.0	269.0	2.0	45	4A0		.16	.81	1.65	17.0				2.46		.67
FAGA062	9824	294.9	297.0	2.1	100	4AC	3.34	.22	2.80	1.15	36.0	.41	7.00	12.70	3.95	19.70	.29
FAGA062	9825	297.0	299.0	2.0	100	4AC		.15	.53	.67	14.0				1.20		.56
FAGA070	9827	62.0	63.2	1.2	100	4A3	3.33	.11	1.61	2.60	33.0	1.10	1.10	14.60	4.21	15.70	.62
FAGA070	9828	63.2	64.8	1.6	94	4A34	3.38	.09	3.40	6.10	51.0	.89	1.10	13.70	9.50	14.80	.64
FAGA070	9830	66.6	67.4	.8	100	4AE1	2.94	.04	1.58	3.70	30.0	.34	1.28	2.53	5.28	3.81	.70
FAGA070	9831	67.4	67.6	.2	100	5C3	2.98	.02	.15	.31	5.0	.27	5.30	2.42	.46	7.72	.67
FAGA070	9832	67.6	69.8	2.2	95	4L14	3.00	.05	.94	1.38	18.0	.34	2.76	4.70	2.32	7.46	.59
FAGAG70	9833	72.3	73.5	1.2	92	4L14	2.93	.04	1.50	4.30	32.0	.48	1.10	3.20	5.80	4.30	.74
FAGA070	9834	73.5	75.0	1.5	100	4A14	3.03	.04	1.60	4.50	34.0	.41	.96	4.53	6.10	5.49	.74
FAGA070	9835	75.0	76.4	1.4	86	4A14	3.05	.04	2.30	5.70	41.0	.48	1.14	3.46	8.00	4.60	.71

DDH	SAMPLE	---DEPTHS---	INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAO	PB+ZN	PC+PY	ZN
		FROM TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGA070	9836	76.4	78.6	2.2	95	4L1	3.10	.06	1.24	.83	30.0	.55	1.42	9.50	2.07	10.92	.40
FAGA070	9837	78.6	79.2	.6	100	4L1	2.97	.03	1.44	3.50	28.0	.34	.86	1.80	4.94	2.66	.71
FAGA070	9839	81.7	83.9	2.2	100	4A1	3.10	.06	1.10	2.90	27.0	.48	1.42	7.00	4.00	8.42	.73
FAGA070	9840	83.9	86.1	2.2	100	4A1	3.12	.06	.99	3.60	21.0	.48	2.71	7.50	4.59	10.21	.78
FAGA070	9841	86.1	88.4	2.3	100	4A1	3.16	.06	1.04	2.60	22.0	.55	1.60	9.50	3.64	11.10	.71
FAGA070	9842	96.8	98.9	2.1	100	3G2		.02	.47	.75	9.0				1.22		.61
FAGA107	9843	52.8	54.4	1.6	94	4DE4	3.77	.14	7.80	16.00	131.0	1.85	1.99	13.60	23.80	15.59	.67
FAGA107	9844	54.4	54.7	.3	100	4G4	4.51	.14	4.00	10.20	59.0	1.78	1.39	22.40	14.20	23.79	.72
FAGA107	9845	54.7	55.5	.8	75	4E4	4.39	.01	.43	5.30	12.0	.75	10.01	29.80	5.73	39.81	.92
FAGA107	9846	55.5	57.4	1.9	100	4GE	4.53	.03	2.06	5.10	39.0	.69	1.20	21.10	7.16	22.30	.71
FAGA107	9847	57.4	57.9	.5	100	4E4	4.75	.10	6.30	17.00	83.0	1.44	3.21	25.90	23.30	29.11	.73
FAGA107	9848	57.9	58.6	.7	100	4G4	4.76	.04	3.00	9.70	43.0	1.44	3.35	19.60	12.70	22.95	.76
FAGA107	9849	58.6	60.4	1.8	100	4E64	4.57	.08	3.50	8.40	63.0	1.23	2.20	27.90	11.90	30.10	.71
FAGA107	9850	60.4	61.2	.8	100	4D3	3.39	.11	4.60	12.50	73.0	1.37	1.23	12.80	17.10	14.03	.73
FAGA096	9851	61.5	62.6	1.1	100	4D0	3.35	.04	3.80	8.20	59.0	.69	1.23	11.90	12.00	13.13	.68
FAGA096	9852	62.6	64.6	2.0	100	4A4	3.31	.08	2.60	5.90	47.0	.48	2.50	12.30	8.50	14.80	.69
FAGA096	9853	64.6	66.6	2.0	85	4A4	3.33	.07	1.64	6.00	35.0	.07	3.92	11.70	7.64	15.62	.79
FAGA096	9854	66.6	69.1	2.5	80	4A4	3.67	.03	3.30	10.70	64.0	.21	3.76	14.60	14.00	18.36	.76
FAGA096	9855	89.3	91.3	2.0	100	4A41	3.34	.05	3.00	5.80	50.0	.82	1.73	12.70	8.80	14.43	.66
FAGA096	9856	91.3	93.6	2.3	100	4A42	3.21	.03	2.01	4.40	37.0	.34	1.90	10.70	6.41	12.60	.69
FAGA096	9857	93.6	94.6	1.0	100	4AE	4.11	.05	4.80	13.50	97.0	.69	4.58	19.20	18.30	23.78	.74
FAGA096	9858	134.2	135.3	1.1	100	4AE	4.07	.20	5.90	11.10	121.0	1.30	2.10	21.30	17.00	23.40	.65
FAGA096	9859	135.3	136.9	1.6	75	4E4	4.45	.20	8.70	13.00	123.0	1.65	.88	25.70	21.70	26.58	.60
FAGA096	9860	136.9	141.5	4.6	28	4D4	4.28	.18	9.40	16.30	189.0	1.37	1.02	22.40	25.70	23.42	.63
FAGA096	9861	141.5	143.3	1.8	94	4D4	3.97	.12	7.60	18.20	127.0	.96	1.06	16.10	25.80	17.16	.71
FAGA096	9862	143.3	145.1	1.8	100	4D4	3.78	.05	6.50	16.40	106.0	1.17	1.05	14.70	22.90	15.75	.72
FAGA096	9863	145.1	146.3	1.2	100	4D4	3.84	.21	7.40	24.00	150.0	2.06	1.50	11.30	31.40	12.80	.76
FAGA096	9864	146.3	148.2	1.9	100	4D4	3.49	.05	6.20	14.10	111.0	.96	1.31	10.50	20.30	11.81	.69
FAGA135	9865	47.7	48.9	1.2	100	4H4#	4.58	.10	11.80	10.00	201.0	1.03	12.94	10.80	21.80	23.74	.46
FAGA135	9866	48.9	50.6	1.7	100	4EG4	4.26	.10	11.30	9.70	188.0	1.10	1.80	18.60	21.00	20.40	.46
FAGA135	9867	50.6	51.3	.7	100	4L0	3.18	.07	2.60	3.70	43.0	.55	3.98	4.95	6.30	8.93	.59
FAGA135	9868	51.3	52.8	1.5	100	4EG4#	4.30	.04	17.30	12.20	259.0	1.37	2.31	17.30	29.50	19.61	.41
FAGA135	9869	52.8	53.7	.9	100	4L0	2.91	.04	.98	1.20	18.0	.55	2.60	4.12	2.18	6.72	.55
FAGA135	9870	53.7	54.5	.8	100	4A4	2.99	.07	3.20	5.40	53.0	.69	3.53	5.20	8.60	8.73	.63
FAGA135	9871	54.5	56.4	1.9	100	4G4#	4.21	.04	10.80	10.50	180.0	.89	1.67	16.40	21.30	18.07	.49
FAGA135	9872	56.4	58.3	1.9	100	4G4#	4.28	.05	14.10	13.80	240.0	.96	2.25	15.20	27.90	17.45	.49
FAGA135	9873	75.5	76.6	1.1	45	4L14		.03	5.20	8.40	80.0				13.60		.62
FAGA135	9874	132.7	135.0	2.3	100	4A4	3.21	.05	2.30	3.90	42.0	.69	1.86	12.90	6.20	14.76	.63
FAGA135	9875	135.0	136.0	1.0	100	5D4*	2.95	.03	.60	.94	12.0	.27	5.75	3.65	1.54	9.40	.61
FAGA135	9876	136.0	136.7	.7	100	4GHE	3.97	.08	6.30	6.10	104.0	.55	10.79	6.50	12.40	17.29	.49
FAGA135	9877	136.7	138.3	1.6	100	4GCL	3.48	.08	2.30	3.30	39.0	.62	2.25	11.30	5.60	13.55	.59
FAGA135	9878	138.3	140.3	2.0	95	4G48	4.40	.06	4.50	6.30	68.0	1.23	3.75	16.30	10.80	20.05	.58
FAGA135	9879	140.3	142.3	2.0	100	4G48	4.38	.06	7.60	7.50	102.0	.69	3.90	15.60	15.10	19.50	.50
FAGA135	9880	142.3	144.3	2.0	95	4G48	4.17	.15	4.30	7.00	84.0	.75	1.71	16.60	11.30	18.31	.62
FAGA135	9881	144.3	146.4	2.1	95	4G48	4.05	.06	3.90	7.40	65.0	.69	2.40	12.40	11.30	14.80	.65
FAGA135	9882	146.4	147.3	.9	100	4E48	4.37	.19	8.60	6.90	118.0	1.44	6.48	25.90	15.50	32.38	.45
FAGA135	9883	147.3	149.1	1.8	94	4D48	3.84	.17	11.60	5.10	145.0	2.54	10.98	14.10	16.70	25.08	.31
FAGA135	9884	149.1	151.7	2.6	96	4CLE	3.38	.19	1.03	1.11	22.0	1.51	4.89	19.40	2.14	24.29	.52
FAGA135	9885	151.7	154.5	2.8	100	4A31	3.21	.19	.47	.58	12.0	1.65	1.78	15.80	1.05	17.58	.55
FAGA135	9886	154.5	156.6	2.1	100	4C09		.26	.21	.34	12.0				.55		.62

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAC	PB+ZN	PC+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGA135	9887	156.6	158.7	2.1	100	4C09		.29	.06	.04	8.0					.10		.40
FAGA135	9888	158.7	160.7	2.0	100	4C09		.61	.12	.19	12.0					.31		.61
FAGA135	9889	160.7	161.6	.9	89	5D0		.14	.30	.28	11.0					.58		.48
FAGA135	9890	161.6	164.2	2.6	100	4C39		.20	.48	.50	13.0					.98		.51
FAGA135	9891	164.2	166.8	2.6	81	4C798		.41	.59	.96	19.0					1.55		.62
FAGA135	9892	166.8	169.4	2.6	96	4C798		.20	.20	.22	8.0					.42		.52
FAGA135	9893	169.4	172.0	2.6	100	4C798		.40	.10	.10	7.0					.20		.50
FAGA135	9894	172.0	174.5	2.5	100	4C798		.30	.27	.47	9.0					.74		.64
FAGU133	9898	.0	3.0	3.0	43	4GE4	4.88	.19	4.60	8.30	85.0	1.23	2.50	23.00		12.90	25.50	.64
FAGU133	9899	3.0	5.0	2.0	100	4EG4	5.03	.07	4.30	8.80	87.0	.62	1.10	12.00		13.10	13.10	.67
FAGU133	9900	5.0	7.0	2.0	100	4GE4	4.84	.11	3.90	7.90	73.0	.48	1.12	16.90		11.80	18.02	.67
FAGU106	9901	100.0	102.0	2.0	75	4D4	2.93	.10	5.00	6.60	94.0	.89	2.35	17.50		11.60	19.85	.57
FAGU106	9902	102.0	104.0	2.0	80	4D4	3.01	.07	7.70	9.20	116.0	.96	1.65	17.30		16.90	18.95	.54
FAGU106	9903	104.0	106.0	2.0	55	4A4	3.34	.04	2.30	5.30	35.0	.89	1.60	13.70		7.60	15.30	.70
FAGU106	9904	106.0	108.0	2.0	100	4A4	3.20	.04	1.80	4.40	31.0	.89	1.52	10.90		6.20	12.42	.71
FAGU106	9905	108.0	110.0	2.0	85	4A4	3.15	.06	1.62	3.50	30.0	.69	1.45	12.70		5.12	14.15	.68
FAGU106	9906	110.0	111.3	1.3	92	4A4	3.01	.04	1.46	3.40	26.0	.41	1.42	7.24		4.86	8.66	.70
FAGU106	9907	111.3	113.3	2.0	80	4A0	3.12	.04	1.16	2.40	23.0	.55	1.59	9.60		3.56	11.19	.67
FAGU106	9908	113.3	115.3	2.0	100	4A0	3.31	.04	.92	1.74	22.0	.55	1.32	15.60		2.66	16.92	.65
FAGU106	9909	115.3	117.3	2.0	100	4A0	3.16	.03	.97	3.10	19.0	.55	2.22	9.67		4.07	11.89	.76
FAGU106	9910	117.3	119.3	2.0	100	4A0	3.09	.03	.95	2.40	21.0	.55	2.05	8.33		3.35	10.38	.72
FAGU106	9911	119.3	121.9	2.6	100	4A0	3.20	.04	1.03	3.70	23.0	.69	1.34	10.90		4.73	12.24	.78
FAGU106	9912	121.9	123.5	1.6	100	4A4	3.21	.05	1.22	4.70	29.0	.75	1.28	10.80		5.92	12.08	.79
FAGU106	9913	123.5	125.3	1.8	100	4A4	3.15	.04	1.54	5.60	42.0	.75	1.34	9.24		7.14	10.58	.78
FAGU123	9914	.0	2.9	2.9	69	4E4	4.56	.23	3.50	8.00	81.0	1.71	2.92	32.00		11.50	34.92	.70
FAGU123	9915	2.9	4.9	2.0	90	4GE4	4.67	.07	3.90	8.80	82.0	1.10	.91	10.60		12.70	11.51	.69
FAGU123	9916	4.9	6.4	1.5	100	4GE4	4.60	.10	3.50	7.60	62.0	.82	.79	13.70		11.10	14.49	.68
FAGU123	9917	6.4	8.4	2.0	100	4GE4	4.83	.17	5.60	8.80	94.0	1.03	1.07	23.80		14.40	24.87	.61
FAGU123	9918	8.4	10.4	2.0	100	4GE4	4.69	.08	2.70	6.40	60.0	.69	1.06	20.60		9.10	21.66	.70
FAGU123	9919	10.4	12.4	2.0	80	4GE4	4.56	.02	1.70	6.20	38.0	.34	.59	8.18		7.90	8.77	.78
FAGU123	9920	12.4	14.4	2.0	100	4GE4	4.51	.08	2.00	6.50	55.0	.62	.81	19.60		8.50	20.41	.76
FAGU123	9921	14.4	16.8	2.4	100	4GE4	4.70	.10	3.00	6.90	58.0	.55	.73	17.90		9.90	18.63	.70
FAGU123	9922	16.8	18.1	1.3	100	4GE4	4.60	.18	4.50	8.50	96.0	.62	1.99	24.40		13.00	26.39	.65
FAGU123	9923	18.1	20.3	2.2	100	4A0	3.34	.10	1.29	1.59	32.0	.27	1.37	12.20		2.88	13.57	.55
FAGU123	9924	20.3	22.9	2.6	100	4AL	3.51	.07	1.84	1.84	39.0	.14	6.21	11.60		3.68	17.81	.50
FAGU123	9925	22.9	24.4	1.5	100	4E4	4.53	.19	4.30	5.00	107.0	.62	1.61	31.70		9.30	33.31	.54
FAGU123	9926	24.4	25.8	1.4	100	4EL	4.13	.06	3.00	3.10	61.0	1.37	2.04	27.80		6.10	29.84	.51
FAGU123	9927	31.0	33.5	2.5	100	4E46	4.63	.09	4.70	8.20	80.0	1.10	.99	23.00		12.90	23.99	.64
FAGU123	9928	33.5	34.3	.8	87	4GL	3.62	.04	1.71	4.10	32.0	.27	7.70	9.50		5.81	17.20	.71
FAGU123	9929	45.7	47.9	2.2	100	4D45	2.95	.06	10.90	20.20	182.0	2.19	3.23	7.25		31.10	10.48	.65
FAGU123	9930	47.9	50.4	2.5	100	4D4	3.87	.07	10.30	21.10	155.0	1.92	2.70	12.80		31.40	15.50	.67
FAGU123	9931	50.4	51.8	1.4	100	4DEKL	4.04	.08	5.80	11.60	79.0	1.51	2.51	21.30		17.40	23.81	.67
FAGU123	9932	51.8	54.2	2.4	100	4ED	4.64	.18	4.90	9.80	88.0	2.19	2.53	32.60		14.70	35.13	.67
FAGU123	9933	54.2	56.2	2.0	100	4A0	3.20	.10	.38	1.01	20.0	.62	1.63	13.50		1.39	15.13	.73
FAGU123	9934	56.2	58.2	2.0	100	4A0	3.10	.09	.17	.24	19.0	1.10	1.66	12.20		.41	13.86	.59
FAGU123	9935	58.2	60.2	2.0	90	4A0	3.19	.12	.14	.70	13.0	.62	1.91	14.10		.84	16.01	.83
FAGU123	9936	60.2	62.2	2.0	100	4A0	3.30	.13	.32	.80	18.0	.62	1.64	16.40		1.12	18.04	.71
FAGU123	9937	62.2	64.4	2.2	100	4A4	3.43	.16	1.81	3.80	42.0	1.17	1.93	18.00		5.61	19.93	.68
FAGU123	9938	64.4	66.0	1.6	100	4EA4	3.54	.17	4.50	6.60	65.0	1.65	2.20	15.30		11.10	17.50	.59
FAGU123	9939	66.0	68.0	2.0	100	4A0	3.34	.11	.79	1.27	24.0	.75	1.90	17.30		2.06	19.20	.62

DDH	SAMPLE	----DEPTHS----	INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAO	PB+ZN	PC+PY	ZN
		FROM TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGU123	9940	68.0 70.0	2.0	100	4A0	3.42	.16	.59	1.06	17.0	.82	1.95	20.10		1.65	22.05	.64
FAGU123	9941	70.0 72.0	2.0	100	4A0		.22	.14	.64	11.0					.78		.82
FAGU123	9942	72.0 74.0	2.0	100	4A0		.12	.14	.33	7.0					.47		.70
FAGU123	9943	74.0 76.0	2.0	100	4A0		.19	.12	.63	8.0					.75		.84
FAGU123	9944	76.0 78.0	2.0	100	4A0		.23	.12	.43	9.0					.55		.78
FAGU123	9945	78.0 80.0	2.0	100	4A0		.22	.09	.84	7.0					.93		.90
FAGU123	9946	80.0 81.0	1.0	100	4LCE	3.87	.21	1.52	3.20	36.0	1.78	2.89	26.40		4.72	29.29	.68
FAGU123	9947	81.0 82.0	1.0	100	4D4	2.92	.11	4.30	7.90	78.0	1.65	2.64	16.70		12.20	19.34	.65
FAGU123	9948	101.5 102.1	.6	100	4G#	4.01	.07	3.90	6.30	65.0	.82	1.88	13.10		10.20	14.98	.62
FAGU123	9949	102.1 103.7	1.6	100	4EL#	3.98	.10	4.60	5.70	77.0	1.17	1.71	20.40		10.30	22.11	.55
FAGU123	9950	103.7 105.6	1.9	100	4EG8	4.50	.34	1.87	2.00	33.0	2.40	6.37	31.90		3.87	38.27	.52
FAGA107	9951	61.2 62.9	1.7	100	4E64	4.60	.19	6.60	12.50	109.0	1.65	1.90	28.90		19.10	30.80	.65
FAGA107	9952	62.9 64.2	1.3	100	4D4	3.67	.06	8.70	18.70	148.0	1.23	2.45	9.10		27.40	11.55	.68
FAGA107	9953	64.2 65.6	1.4	100	4D4	3.68	.09	7.40	12.60	125.0	1.23	2.04	11.50		20.00	13.54	.63
FAGA107	9954	65.6 67.9	2.3	96	4E4	5.46	.19	6.70	14.80	96.0	1.23	3.62	26.60		21.50	30.22	.69
FAGA107	9955	67.9 69.8	1.9	100	4DE4	4.35	.04	10.80	20.30	156.0	1.51	2.59	14.20		31.10	16.79	.65
FAGA107	9956	69.8 70.2	.4	100	4E4	4.94	.01	4.30	10.00	61.0	.75	4.64	28.30		14.30	32.94	.70
FAGA107	9957	70.2 71.2	1.0	100	4D4	4.04	.09	8.00	17.20	150.0	1.71	3.37	12.70		25.20	16.07	.68
FAGA107	9958	71.2 73.2	2.0	100	4CE	3.84	.30	.57	1.68	27.0	1.10	2.18	23.70		2.25	25.88	.75
FAGA107	9959	73.2 74.5	1.3	92	4CA	3.66	.28	.22	1.31	17.0	.48	2.55	18.80		1.53	21.35	.86
FAGA107	9960	74.5 75.7	1.2	100	4CA		.27	.17	.26	15.0					.43		.60
FAGA107	9961	75.7 78.1	2.4	100	4A13		.19	.93	1.34	21.0					2.27		.59
FAGA107	9962	78.1 79.3	1.2	100	4C35		.20	.89	.78	24.0					1.67		.47
FAGA107	9963	79.3 81.3	2.0	100	4A13		.19	.21	.52	10.0					.73		.71
FAGA107	9964	81.3 83.4	2.1	100	4A13		.12	.25	.25	16.0					.50		.50
FAGA107	9965	83.4 84.7	1.3	100	4A13		.16	.15	.39	9.0					.54		.72
FAGA107	9966	84.7 87.1	2.4	100	4A13		.18	.23	.92	11.0					1.15		.80
FAGA107	9967	87.1 88.2	1.1	91	4C0		.23	.32	.77	13.0					1.09		.71
FAGA107	9968	88.2 89.7	1.5	100	4CA		.30	.11	.50	13.0					.61		.82
FAGA107	9969	89.7 91.2	1.5	100	4CE		.24	.59	1.20	19.0					1.79		.67
FAGA107	9970	91.2 92.8	1.6	100	4CE		.28	.61	1.02	22.0					1.63		.63
FAGA107	9971	92.8 94.8	2.0	100	4A0		.20	.07	.25	11.0					.32		.78
FAGA107	9972	94.8 96.8	2.0	100	4A0		.18	.06	.40	11.0					.46		.87
FAGA107	9973	96.8 98.8	2.0	75	4A0		.27	.08	.43	16.0					.51		.84
FAGA107	9974	98.8 100.8	2.0	75	4A0		.13	.05	.45	10.0					.50		.90
FAGA107	9975	100.8 102.8	2.0	90	4A0		.34	.10	.46	13.0					.56		.82
FAGA107	9976	102.8 104.8	2.0	85	4A0		.28	.10	.25	12.0					.35		.71
FAGA107	9977	104.8 106.8	2.0	55	4A0		.18	.06	.18	9.0					.24		.75
FAGA107	9978	106.8 108.7	1.9	79	4A0		.24	.03	.16	5.0					.19		.84
FAGA107	9979	108.7 110.7	2.0	35	4A1		.22	.05	.13	7.0					.18		.72
FAGA107	9980	110.7 112.3	1.6	75	4A1		.15	.04	.08	5.0					.12		.67
FAGA107	9981	112.3 113.9	1.6	100	4A1		.12	.08	.26	3.0					.34		.76
FAGA107	9982	113.9 114.8	.9	100	4A13		.17	.77	.34	13.0					1.11		.31
FAGA107	9983	114.8 116.8	2.0	100	4E0	4.47	.36	.88	1.15	22.0	1.65	.78	44.40		2.03	45.18	.57
FAGA107	9984	116.8 118.7	1.9	100	4E0	4.47	.28	1.27	1.82	26.0	1.71	1.07	43.60		3.09	44.67	.59
FAGA107	9985	118.7 120.9	2.2	100	4E\$	4.63	.20	2.17	4.40	55.0	1.85	1.07	39.20		6.57	40.27	.67
FAGA107	9986	120.9 121.5	.6	100	4E0	4.91	.23	.44	.56	15.0	1.85	1.11	44.60		1.00	45.71	.56
FAGA107	9987	121.5 122.1	.6	100	4ED4	4.38	.06	10.80	15.60	180.0	1.65	1.92	21.20		26.40	23.12	.59
FAGA107	9988	122.1 123.5	1.4	100	4A13	3.31	.14	1.60	2.50	30.0	2.06	1.19	17.60		4.10	18.79	.61
FAGA107	9989	123.5 123.8	.3	100	4D4	3.81	.05	4.90	6.00	73.0	2.19	2.32	18.60		10.90	20.92	.55

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAO	PB+ZN	PO+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGA107	9990	168.5	169.9	1.4	100	4L14		.13	.82	.43	14.0					1.25		.34
FAGA107	9991	169.9	171.3	1.4	100	4L14		.12	.51	.21	9.0					.72		.29
FAGA107	9992	171.3	172.3	1.0	70	4H0		.22	3.70	3.69	39.0					7.39		.50
FAGU106	9993	.0	1.7	1.7	65	4D4	4.01	.01	8.70	19.50	162.0	1.44	2.03	13.10		28.20	15.13	.69
FAGU106	9994	1.7	3.5	1.8	100	4D4	2.89	.03	7.70	19.10	136.0	1.17	1.79	10.60		26.80	12.39	.71
FAGU106	9995	3.5	4.6	1.1	91	4D4	3.50	.03	4.90	14.90	83.0	.96	2.19	8.14		19.80	10.33	.75
FAGU106	9996	4.6	6.2	1.6	63	4D4	2.97	.04	7.90	17.70	140.0	1.30	2.09	10.70		25.60	12.79	.69
FAGU106	9997	6.2	9.2	3.0	23	4E4	4.86	.17	9.20	17.20	177.0	2.74	1.43	26.80		26.40	28.23	.65
FAGU106	9998	9.2	10.7	1.5	87	4E4	4.70	.08	9.90	16.10	161.0	1.58	1.56	25.60		26.00	27.16	.62
FAGU106	9999	10.7	13.8	3.1	45	4E4	4.76	.19	9.10	15.50	148.0	2.47	1.39	28.20		24.60	29.59	.63
FAGU106	10000	13.8	15.2	1.4	50	4A0	3.54	.13	1.48	1.65	27.0	.69	1.27	13.30		3.13	14.57	.53
FAGU123	11001	105.6	107.0	1.4	100	4E46	4.47	.21	4.60	1.68	35.0	1.78	5.19	32.20		6.28	37.39	.27
FAGU123	11002	107.0	108.7	1.7	100	4E46	4.46	.16	8.40	4.80	89.0	1.37	9.34	23.10		13.20	32.44	.36
FAGU123	11003	108.7	110.8	2.1	100	4E0		.42	.85	.62	20.0					1.47		.42
FAGU123	11004	110.8	112.8	2.0	100	4CE0		.35	.24	.14	15.0					.38		.37
FAGU123	11005	112.8	114.8	2.0	100	4CE0		.43	.25	.18	18.0					.43		.42
FAGU123	11006	114.8	116.8	2.0	100	4CE0		.32	.18	.15	17.0					.33		.45
FAGU123	11007	116.8	118.9	2.1	100	4CE0		.19	1.08	2.40	24.0					3.48		.69
FAGU090	11008	.0	3.0	3.0	23	4E4	4.67	.17	8.50	10.10	119.0	1.92	1.05	27.80		18.60	28.85	.54
FAGU090	11009	3.0	6.1	3.1	35	4E4	4.70	.22	9.20	19.70	138.0	2.40	1.51	23.70		28.90	25.21	.68
FAGU090	11010	6.1	9.2	3.1	52	4E4	4.63	.11	7.20	13.20	121.0	1.71	1.10	26.80		20.40	27.90	.65
FAGU090	11011	9.2	12.2	3.0	57	4E4	4.64	.25	6.60	10.90	113.0	2.06	1.10	28.80		17.50	29.90	.62
FAGU090	11012	12.2	13.7	1.5	100	4A4	3.70	.16	2.90	4.00	62.0	.89	1.28	20.50		6.90	21.78	.58
FAGU090	11013	13.7	15.2	1.5	67	4A4	4.29	.13	3.30	5.40	61.0	.96	1.28	21.60		8.70	22.88	.62
FAGU090	11014	15.2	17.0	1.8	67	4E4	3.49	.12	2.50	4.10	52.0	1.03	1.09	15.30		6.60	16.39	.62
FAGU090	11015	17.0	18.3	1.3	100	4A0	3.07	.01	.06	.07	4.0	.14	3.38	1.22		.13	4.60	.54
FAGU119	11020	.0	4.6	4.6	37	4GE4	4.84	.13	6.00	12.00	114.0	1.30	2.34	18.80		18.00	21.14	.67
FAGU119	11021	4.6	6.1	1.5	93	4GE4	5.38	.11	4.80	8.30	91.0	1.10	.68	15.90		13.10	16.58	.63
FAGU119	11022	6.1	7.6	1.5	87	4GE4	4.94	.11	4.70	9.20	91.0	.62	1.03	16.70		13.90	17.73	.66
FAGU119	11023	7.6	8.6	1.0	100	4GE4	4.84	.17	5.40	9.80	96.0	.89	1.71	16.60		15.20	18.31	.64
FAGU119	11024	57.9	59.4	1.5	100	4D5	4.11	.28	2.90	4.30	50.0	1.51	2.84	21.30		7.20	24.14	.60
FAGU119	11025	59.4	60.7	1.3	92	4A0	4.23	.22	.10	.41	15.0	1.03	2.27	18.50		.51	20.77	.80
FAGU119	11026	60.7	62.7	2.0	100	4EDA	4.63	.20	7.20	11.30	120.0	1.85	2.18	16.20		18.50	18.38	.61
FAGU119	11027	62.7	64.7	2.0	100	4AG	4.21	.27	2.40	3.00	43.0	1.23	1.52	21.60		5.40	23.12	.56
FAGU119	11028	64.7	66.8	2.1	100	4CD	3.61	.16	2.50	3.20	46.0	1.37	2.93	18.70		5.70	21.63	.56
FAGU119	11029	66.8	68.8	2.0	100	4C0	4.66	.28	1.13	.64	31.0	1.71	2.45	20.60		1.77	23.05	.36
FAGU119	11030	68.8	70.9	2.1	95	4C0	3.60	.17	.23	1.70	16.0	1.30	3.10	20.10		1.93	23.20	.88
FAGU119	11031	70.9	73.4	2.5	100	4ALC	3.49	.46	.14	.67	16.0	.69	2.47	19.80		.81	22.27	.83
FAGU119	11032	73.4	75.1	1.7	100	4C0	3.40	.32	.18	.74	17.0	.96	2.54	17.20		.92	19.74	.80
FAGU119	11033	75.1	76.2	1.1	73	4DA4	3.66	.13	5.80	7.40	81.0	1.99	2.80	15.20		13.20	18.00	.56
FAGA063	11034	78.7	80.8	2.1	100	4E8#	3.88	.19	1.60	1.38	31.0	.96	22.30	7.22		2.98	29.52	.46
FAGA063	11035	80.8	83.2	2.4	75	4D0	3.62	.11	1.77	2.40	30.0	.62	16.20	5.00		4.17	21.20	.58
FAGA063	11036	83.2	85.0	1.8	89	4A3		.09	.50	.50	15.0					1.00		.50
FAGA063	11037	85.0	86.9	1.9	95	4A3		.19	.38	.27	14.0					.65		.42
FAGA063	11038	86.9	88.7	1.8	100	4A3		.18	.17	.12	13.0					.29		.41
FAGA063	11039	88.7	90.4	1.7	100	4A3		.19	.26	.19	16.0					.45		.42
FAGA063	11040	90.4	92.2	1.8	100	4C\$		.18	.12	.16	10.0					.28		.57
FAGA063	11041	92.2	94.3	2.1	76	4A3		.20	.21	.33	12.0					.54		.61
FAGA063	11042	94.3	96.4	2.1	100	4A3		.20	.13	.27	12.0					.40		.68

DDH	SAMPLE	---DEPTHS---	INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAO	PB+ZN	PO+PY	ZN
		FROM TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGA063	11043	96.4 98.4	2.0	95	4C0		.30	.36	.72	15.0					1.08		.67
FAGA063	11044	100.1 101.4	1.3	100	4E#4	4.10	.40	5.10	7.20	75.0	2.33	29.60	3.22		12.30	32.82	.59
FAGA063	11045	101.4 102.7	1.3	100	4E#4	4.62	.32	5.30	6.70	79.0	1.71	27.70	3.68		12.00	31.38	.56
FAGA063	11046	102.7 104.4	1.7	100	4G4#	4.70	.09	3.80	6.80	74.0	.62	14.70	.78		10.60	15.48	.64
FAGA063	11047	104.4 106.1	1.7	100	4G4#	4.82	.06	4.10	6.80	72.0	.62	20.30	.81		10.90	21.11	.62
FAGA063	11048	106.1 107.7	1.6	100	4G4#	4.67	.06	4.40	6.00	70.0	.69	19.20	.90		10.40	20.10	.58
FAGA063	11049	107.7 108.1	.4	75	4E#	4.82	.16	4.30	6.30	71.0	1.51	36.20	1.12		10.60	37.32	.59
FAGA063	11050	108.1 108.7	.6	100	4K0	4.45	.04	.64	1.18	18.0	.62	35.30	2.47		1.82	37.77	.65
FAGA063	11051	108.7 109.9	1.2	42	4E64	4.71	.13	4.90	8.70	79.0	1.58	27.20	1.44		13.60	28.64	.64
FAGA063	11052	109.9 111.2	1.3	54	4E64	4.05	.04	3.80	6.60	51.0	.55	16.40	4.38		10.40	20.78	.63
FAGA063	11053	111.8 112.9	1.1	73	4G4	4.62	.06	4.00	6.80	54.0	.48	11.80	1.89		10.80	13.69	.63
FAGA063	11054	113.2 114.1	.9	100	4C3	3.39	.19	1.68	2.90	25.0	1.03	14.50	4.76		4.58	19.26	.63
FAGA063	11055	114.6 115.4	.8	88	4E1		.43	.23	.57	14.0					.80		.71
FAGA063	11056	115.4 117.0	1.6	100	4C3		.33	.16	.38	10.0					.54		.70
FAGA063	11057	117.0 118.7	1.7	94	4C3		.19	.16	.42	10.0					.58		.72
FAGA063	11058	118.7 120.3	1.6	100	4C3		.31	.30	.87	14.0					1.17		.74
FAGA063	11059	120.3 120.7	.4	100	4C#	3.75	.19	1.05	2.40	20.0	.89	22.40	2.70		3.45	25.10	.70
FAGA063	11060	120.7 122.2	1.5	87	4C3	3.39	.15	.92	1.90	20.0	.96	9.50	9.10		2.82	18.60	.67
FAGA063	11061	122.2 123.4	1.2	92	4C0		.32	.08	.31	11.0					.39		.79
FAGA063	11062	123.4 125.5	2.1	100	4A0		.26	.07	.26	11.0					.33		.79
FAGA063	11063	125.5 125.9	.4	75	4A0		.19	.05	.29	11.0					.34		.85
FAGA063	11064	125.9 128.0	2.1	100	4A0		.30	.09	.32	11.0					.41		.78
FAGA063	11065	128.0 130.0	2.0	100	4A0		.36	.07	.23	10.0					.30		.77
FAGA063	11066	130.0 130.6	.6	100	4D35	3.45	.25	2.40	4.20	34.0	1.10	15.40	5.00		6.60	20.40	.64
FAGA063	11067	98.4 100.1	1.7	100	4EL	3.47	.04	2.20	4.30	27.0	.62	13.00	5.35		6.50	18.35	.66
FAGA063	11068	130.6 131.5	.9	100	4E#4	4.59	.15	4.40	7.20	62.0	1.23	31.60	2.55		11.60	34.15	.62
FAGA063	11069	131.5 132.2	.7	86	4G4#	4.36	.08	5.80	7.00	74.0	.55	17.50	2.26		12.80	19.76	.55
FAGA063	11070	132.8 133.7	.9	100	4C\$		.16	1.20	1.60	16.0					2.80		.57
FAGA063	11071	145.4 147.3	1.9	100	4C3	3.64	.10	.97	1.15	15.0	.27	10.60	6.41		2.12	17.01	.54
FAGA063	11072	147.3 147.9	.6	83	4E#4	4.44	.08	4.30	3.30	38.0	.69	17.00	4.06		7.60	21.06	.43
FAGA063	11073	147.9 149.2	1.3	100	4A0		.19	.14	.14	9.0					.28		.50
FAGA063	11074	149.2 150.5	1.3	100	4A0		.15	.13	.19	10.0					.32		.59
FAGA063	11075	150.5 151.3	.8	100	4E1		.02	.17	.29	11.0					.46		.63
FAGA063	11076	151.3 152.6	1.3	92	4A0		.36	.05	.12	8.0					.17		.71
FAGA063	11077	152.6 154.0	1.4	93	4A0		.17	.43	.54	13.0					.97		.56
FAGA063	11078	154.0 155.3	1.3	100	4C0		.25	2.30	1.76	33.0					4.06		.43
FAGA063	11079	155.3 156.5	1.2	100	4C3	4.47	.10	1.59	2.04	35.0	1.37	25.30	5.18		3.63	30.48	.56
FAGA063	11080	156.5 158.3	1.8	94	4A0		.19	.16	.29	9.0					.45		.64
FAGA063	11081	158.3 159.9	1.6	100	4C83		.16	.98	1.14	25.0					2.12		.54
FAGA063	11082	159.9 161.5	1.6	100	4C83	4.94	.32	1.67	1.34	32.0	.96	17.70	12.60		3.01	30.30	.45
FAGA063	11083	161.5 163.2	1.7	94	4C83	3.83	.17	1.19	1.40	33.0	.75	7.40	18.40		2.59	25.80	.54
FAGA063	11084	163.2 164.8	1.6	100	4C83	3.91	.28	1.30	1.48	31.0	.55	8.70	19.80		2.78	28.50	.53
FAGA063	11085	164.8 166.5	1.7	94	4C83	3.75	.24	1.49	1.42	29.0	.82	9.30	17.60		2.91	26.90	.49
FAGA063	11086	166.5 167.5	1.0	100	4C3	3.31	.23	.35	.37	17.0	.69	3.66	16.30		.72	19.96	.51
FAGA063	11087	167.5 167.9	.4	100	4E64	4.40	.16	4.90	6.10	64.0	.55	2.14	20.90		11.00	23.04	.55
FAGA063	11088	167.9 168.6	.7	100	4E14	3.65	.14	2.60	3.10	38.0	.55	3.93	18.10		5.70	22.03	.54
FAGA063	11089	168.6 169.3	.7	100	4A3	3.59	.39	.13	.19	13.0	.69	2.69	21.10		.32	23.79	.59
FAGA063	11090	169.3 170.0	.7	86	4C3	3.72	.26	3.30	4.00	45.0	.82	5.03	19.50		7.30	24.53	.55
FAGA063	11091	170.0 170.5	.5	100	4E8	5.50	.36	.66	1.30	20.0	1.10	31.70	5.88		1.96	37.58	.66
FAGA063	11092	170.5 172.1	1.6	94	4C0		.22	1.35	1.80	29.0					3.15		.57

DDH	SAMPLE	---DEPTHS---	INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAO	PS+ZN	PC+PY	ZN
		FROM TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGA063	11093	172.1	174.0	1.9	100	4A0	.18	.12	.29	10.0					.41		.71
FAGA063	11094	174.0	176.0	2.0	100	4A0	.22	.04	.08	10.0					.12		.67
FAGA063	11095	176.0	178.1	2.1	95	4A0	.11	.06	.15	13.0					.21		.71
FAGU131	11096	.5	1.5	1.0	50	4G4	4.67	.09	3.80	6.70	80.0	1.03	.80	23.00	10.50	23.80	.64
FAGU131	11097	1.5	3.2	1.7	59	4GE#	4.75	.11	4.70	9.40	89.0	.96	1.44	19.30	14.10	20.74	.67
FAGU131	11098	3.2	4.6	1.4	100	4G4	4.51	.08	4.40	8.40	105.0	.82	.67	11.60	12.80	12.27	.66
FAGU131	11099	4.6	5.5	.9	100	4E4	4.64	.22	5.70	10.50	109.0	1.23	3.30	28.70	16.20	32.00	.65
FAGU131	11100	15.3	16.8	1.5	67	4EGD	4.20	.17	5.10	7.50	89.0	1.58	2.21	21.10	12.60	23.31	.60
FAGU133	11101	7.0	8.5	1.5	100	4GE4	5.19	.08	4.70	9.10	84.0	.96	.68	14.40	13.80	15.08	.66
FAGU133	11102	8.5	10.2	1.7	100	4E4	4.94	.14	5.90	9.70	116.0	1.51	2.30	31.40	15.60	33.70	.62
FAGU133	11103	10.2	12.1	1.9	100	4G4	4.64	.15	5.30	8.90	94.0	.96	.73	29.60	14.20	30.33	.63
FAGU133	11104	12.1	14.5	2.4	100	4E46	5.13	.14	2.30	4.40	70.0	.75	.59	34.10	6.70	34.69	.66
FAGU133	11105	14.5	16.3	1.8	100	4G4	4.64	.08	3.40	7.50	63.0	.75	.44	22.90	10.90	23.34	.69
FAGU133	11106	16.3	18.2	1.9	100	4EKG	4.50	.26	4.80	6.70	113.0	1.44	1.32	29.00	11.50	30.32	.58
FAGU133	11107	47.3	49.3	2.0	100	4DA4	3.56	.08	10.00	19.00	152.0	1.51	2.50	7.00	29.00	9.50	.66
FAGU133	11108	49.3	51.3	2.0	100	4DA4	3.74	.06	9.20	17.70	151.0	1.44	3.27	8.90	26.90	12.17	.66
FAGU133	11109	51.3	53.1	1.8	100	4DA4	3.57	.08	8.20	14.60	131.0	1.58	3.08	8.40	22.80	11.48	.64
FAGU133	11110	54.5	56.0	1.5	100	4DA4	3.54	.26	5.00	5.70	89.0	2.13	1.59	18.50	10.70	20.09	.53
FAGU133	11111	56.0	57.3	1.3	100	4E4	4.17	.23	2.30	4.90	45.0	1.17	2.84	30.30	7.20	33.14	.68
FAGU133	11112	57.3	59.2	1.9	100	4A4	3.83	.08	4.10	8.60	68.0	1.30	2.60	15.90	12.70	18.50	.68
FAGU133	11113	59.2	61.2	2.0	95	4A0	3.41	.21	1.00	2.50	23.0	.75	1.64	18.10	3.50	19.74	.71
FAGU133	11114	61.2	63.3	2.1	100	4A0	3.18	.16	.17	1.12	12.0	.41	1.48	13.50	1.29	14.98	.87
FAGU133	11115	63.3	64.0	.7	71	4E0	3.55	.13	1.66	2.50	27.0	.21	6.80	13.40	4.16	20.20	.60
FAGU133	11116	64.0	67.1	3.1	74	4A0	3.23	.43	.14	.87	19.0	.41	1.48	13.30	1.01	14.78	.86
FAGU133	11117	67.1	70.0	2.9	79	4A0		.20	.18	.80	16.0				.98		.82
FAGU133	11118	93.0	96.3	3.3	91	4EL	4.07	.48	.26	2.60	23.0	.48	2.55	33.30	2.86	35.85	.91
FAGU133	11119	114.3	115.8	1.5	100	4G4	4.12	.18	6.20	8.40	106.0	1.51	2.05	12.80	14.60	14.85	.58
FAGU133	11120	115.8	117.6	1.8	100	4EG8	5.56	.21	2.80	3.10	41.0	.75	5.10	26.10	5.90	31.20	.53
FAGU121	11121	.0	2.7	2.7	19	4EGC	4.28	.02	2.90	5.40	62.0	.75	1.11	25.40	8.30	26.51	.65
FAGU121	11122	40.5	42.5	2.0	100	4A0	3.57	.06	1.44	1.60	27.0	.27	1.16	3.60	3.04	4.76	.53
FAGU121	11123	42.5	44.6	2.1	100	4A0	3.56	.06	1.16	1.95	23.0	.34	1.16	3.92	3.11	5.08	.63
FAGU115	11124	8.5	10.7	2.2	68	4E4	4.94	.14	6.00	9.60	156.0	1.92	.72	30.60	15.60	31.32	.62
FAGU115	11125	10.7	13.7	3.0	40	4E4	5.26	.10	4.40	9.10	93.0	1.58	1.05	34.20	13.50	35.25	.67
FAGU115	11126	13.7	15.5	1.8	39	4D4	3.84	.07	5.00	12.50	99.0	1.23	1.14	13.00	17.50	14.14	.71
FAGU115	11127	15.5	17.6	2.1	95	4EKD	5.01	.15	2.90	4.60	51.0	1.17	1.10	39.40	7.50	40.50	.61
FAGU115	11128	17.6	19.1	1.5	93	4EKD	4.83	.11	5.40	9.70	105.0	1.30	1.47	31.50	15.10	32.97	.64
FAGU115	11129	19.1	22.2	3.1	42	4A4	3.46	.09	2.60	4.20	45.0	.96	1.57	12.10	6.80	13.67	.62
FAGU115	11130	24.6	27.0	2.4	100	4A0	3.49	.09	.93	.93	25.0	.55	.63	13.60	1.86	14.23	.50
FAGU115	11131	27.0	30.2	3.2	62	4A4	3.66	.08	2.60	4.90	42.0	.55	1.79	13.10	7.50	14.89	.65
FAGU092	11132	1.0	2.0	1.0	100	4DE4	3.90	.02	8.00	16.20	128.0	1.17	2.19	15.30	24.20	17.49	.67
FAGU092	11133	2.0	3.3	1.3	100	4ED4	4.69	.17	9.40	13.50	166.0	2.81	1.90	27.80	22.90	29.70	.59
FAGU092	11134	3.3	4.6	1.3	100	4ED4	3.41	.05	8.40	12.70	123.0	1.92	2.03	26.00	21.10	28.03	.60
FAGU092	11135	4.6	6.1	1.5	100	4D43	3.79	.01	9.10	15.10	139.0	1.51	1.87	12.50	24.20	14.37	.62
FAGU092	11136	6.1	7.6	1.5	100	4D43	3.67	.02	8.00	14.60	113.0	1.37	2.00	11.70	22.60	13.70	.65
FAGU092	11137	7.6	8.9	1.3	100	4E4	4.64	.06	10.00	18.30	126.0	1.51	2.17	24.20	28.30	26.37	.65
FAGU092	11138	8.9	10.7	1.8	100	4E4	4.73	.07	1.53	7.60	35.0	1.44	4.17	36.70	9.13	40.87	.83
FAGU092	11139	10.7	11.0	.3	100	4E4	4.40	.03	.46	10.90	15.0	.82	11.18	25.90	11.36	37.08	.96
FAGU092	11140	11.0	12.3	1.3	100	4E4	4.40	.12	1.58	10.60	38.0	1.51	5.77	30.10	12.18	35.87	.87
FAGU092	11141	12.3	12.7	.4	100	4E4	3.21	.02	.80	6.10	22.0	.89	3.81	21.80	6.90	25.61	.88
FAGU092	11142	12.7	14.6	1.9	47	4E4*	4.83	.03	1.56	6.30	31.0	1.17	2.28	39.50	7.86	41.78	.80

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAO	PB+ZN	PO+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGU092	11143	14.6	16.6	2.0	95	4E4*	4.86	.15	7.70	16.00	109.0	2.40	1.61	29.90		23.70	31.51	.68
FAGU092	11144	16.6	18.1	1.5	100	4ED4	4.30	.10	7.30	12.30	107.0	2.74	2.37	21.60		19.60	23.97	.63
FAGU092	11145	18.1	19.7	1.6	69	4ED4	4.25	.22	2.20	6.60	39.0	2.40	2.90	28.90		8.80	31.80	.75
FAGU092	11146	19.7	21.2	1.5	73	4DE4	3.87	.08	2.80	6.30	53.0	1.78	2.20	23.70		9.10	25.90	.69
FAGU092	11147	21.2	22.8	1.6	81	4D3	3.71	.11	1.01	4.40	24.0	2.19	2.11	22.30		5.41	24.41	.81
FAGU092	11148	22.8	24.4	1.6	100	4ED	3.61	.09	1.11	4.00	29.0	1.78	1.75	20.90		5.11	22.65	.78
FAGU092	11149	24.4	26.4	2.0	100	4A34	3.69	.09	3.00	5.30	49.0	1.78	1.58	18.90		8.30	20.48	.64
FAGU092	11150	26.4	28.4	2.0	95	4A34	4.03	.16	3.10	5.60	52.0	2.13	1.48	24.20		8.70	25.68	.64
FAGU136	11151	31.0	32.0	1.0	80	4L4	4.24	.22	2.90	2.30	41.0	.48	7.00	16.40		5.20	23.40	.44
FAGU136	11152	32.0	34.6	2.6	69	4G4#	4.72	.09	5.30	5.80	80.0	.69	1.11	23.30		11.10	24.41	.52
FAGU136	11153	39.1	41.1	2.0	65	4GEL	4.94	.20	2.70	2.04	57.0	.96	2.98	33.20		4.74	36.18	.43
FAGU136	11154	41.1	44.2	3.1	52	4E4#	4.83	.23	4.40	3.70	71.0	.89	3.08	35.50		8.10	38.58	.46
FAGU136	11155	44.2	46.2	2.0	50	4G4	4.67	.08	6.30	7.70	98.0	.55	2.84	13.70		14.00	16.54	.55
FAGU136	11156	46.2	48.2	2.0	50	4G4	5.01	.10	6.60	6.80	110.0	.41	3.55	12.70		13.40	16.25	.51
FAGU136	11157	48.2	50.2	2.0	90	4G4	4.86	.06	7.30	7.60	125.0	.41	2.98	10.60		14.90	13.58	.51
FAGU136	11158	50.2	51.7	1.5	100	4G4	4.64	.12	5.60	6.60	90.0	.48	4.39	17.10		12.20	21.49	.54
FAGU136	11159	51.7	53.3	1.6	87	4G4	4.54	.11	6.20	6.60	101.0	.62	1.80	19.70		12.80	21.50	.52
FAGU136	11160	53.3	54.7	1.4	71	4EK8	4.29	.24	4.30	3.60	66.0	.62	5.90	30.10		7.90	36.00	.46
FAGU136	11161	54.7	56.2	1.5	67	4LC	3.38	.13	1.57	1.25	30.0	.48	3.51	12.70		2.82	16.21	.44
FAGU136	11162	56.2	58.2	2.0	50	4EC	3.98	.18	1.67	1.15	33.0	.69	4.50	28.70		2.82	33.20	.41
FAGU136	11163	58.2	60.2	2.0	45	4EC	4.35	.53	2.40	1.35	47.0	1.51	6.48	24.80		3.75	31.28	.36
FAGU136	11164	60.2	61.4	1.2	67	4EC	3.02	.29	1.49	1.33	44.0	1.03	6.70	23.40		2.82	30.10	.47
FAGU127	11165	.0	3.0	3.0	33	4E4	4.83	.12	7.80	12.60	121.0	1.65	2.54	25.70		20.40	28.24	.62
FAGU127	11166	3.0	4.6	1.6		4E4	4.72	.12	9.50	17.90	143.0	2.74	4.47	22.10		27.40	26.57	.65
FAGU127	11167	4.6	5.9	1.3		4ELA	3.19	.04	1.62	2.80	27.0	.82	2.81	6.68		4.42	9.49	.63
FAGU127	11168	5.9	7.3	1.4		4L5	3.16	.05	.70	1.09	15.0	.34	8.12	6.15		1.79	14.27	.61
FAGU127	11169	7.3	8.8	1.5		4G4	4.64	.21	7.10	12.40	117.0	2.67	1.93	16.45		19.50	18.38	.64
FAGU127	11170	8.8	10.6	1.8		4G4	4.81	.30	5.60	13.70	86.0	2.06	2.41	13.70		19.30	16.11	.71
FAGU127	11171	10.6	12.4	1.8		4E4	4.51	.26	5.50	8.20	74.0	2.26	2.86	28.90		13.70	31.76	.60
FAGU127	11172	12.4	13.8	1.4		4L24	3.80	.04	1.61	12.70	38.0	.69	9.23	6.80		14.31	16.03	.89
FAGU127	11173	13.8	15.1	1.3		4G4	4.57	.10	4.80	10.20	104.0	1.51	1.89	12.70		15.00	14.59	.68
FAGU127	11174	15.1	17.1	2.0		4E4	4.75	.11	6.30	12.20	88.0	1.65	3.22	29.10		18.50	32.32	.66
FAGU127	11175	17.1	19.1	2.0		4E4	4.70	.22	4.90	10.00	74.0	2.40	2.54	32.00		14.90	34.54	.67
FAGU127	11176	19.1	21.1	2.0		4E4	4.69	.29	4.40	8.90	60.0	4.53	2.47	32.10		13.30	34.57	.67
FAGU127	11177	21.1	23.1	2.0		4E4	4.57	.21	5.30	10.80	99.0	1.85	2.38	29.80		16.10	32.18	.67
FAGU127	11178	23.1	25.5	2.4		4E4	4.57	.25	6.00	13.50	106.0	2.33	3.31	27.00		19.50	30.31	.69
FAGU127	11179	25.5	26.4	.9		4A0	3.63	.14	2.20	2.70	48.0	1.51	1.75	22.80		4.90	24.55	.55
FAGU127	11180	26.4	27.5	1.1		4C0	3.91	.45	.62	1.84	31.0	1.10	2.21	26.50		2.46	28.71	.75
FAGU127	11181	27.5	29.2	1.7		4A0	3.38	.15	.37	.95	19.0	1.23	1.32	20.20		1.32	21.52	.72
FAGU127	11182	29.2	30.6	1.4		4A4	3.25	.05	4.20	6.70	65.0	1.10	1.15	10.60		10.90	11.75	.61
FAGU127	11183	30.6	32.8	2.2		4A0	2.99	.09	1.27	1.11	25.0	1.03	.66	7.66		2.38	8.32	.47
FAGU127	11184	32.8	35.0	2.2		4AC		.11	.22	.54	9.0					.76		.71
FAGU127	11185	35.0	38.5	3.5		4L2		.05	.42	.75	10.0					1.17		.64
FAGU111	11186	2.4	3.9	1.5	7	4E4	4.83	.36	14.20	25.00	253.0	3.98	1.27	19.10		39.20	20.37	.64
FAGU111	11187	3.9	4.2	.3	100	4K4	3.99	.06	5.60	5.60	63.0	1.58	2.23	24.60		11.20	26.83	.50
FAGU111	11188	4.2	5.6	1.4	57	4E4	4.70	.13	10.50	10.50	94.0	2.06	1.09	32.60		21.00	33.69	.50
FAGU111	11189	5.6	6.7	1.1	64	4D4	3.60	.09	6.60	16.00	106.0	1.58	1.20	11.80		22.60	13.00	.71
FAGU111	11190	6.7	7.8	1.1	100	4D4	3.63	.04	7.90	18.00	122.0	1.37	1.46	12.50		25.90	13.96	.69
FAGU111	11191	7.8	9.4	1.6	56	4E4	4.72	.12	12.10	12.10	132.0	2.47	.83	30.20		24.20	31.03	.50
FAGU111	11192	9.4	9.9	.5	100	4D4	3.52	.01	6.40	16.40	86.0	1.58	1.68	9.47		22.80	11.15	.72

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAO	PB+ZN	PC+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGU111	11193	9.9	11.3	1.4	29	4E4*	4.67	.15	5.00	8.40	108.0	2.26	1.47	34.00		13.40	35.47	.63
FAGU111	11194	11.3	12.7	1.4	43	4E4*	4.84	.19	9.30	9.90	144.0	2.61	1.50	31.00		19.20	32.50	.52
FAGU111	11195	12.7	14.2	1.5	53	4E4*	4.80	.06	3.40	4.10	69.0	.75	1.43	41.00		7.50	42.43	.55
FAGU111	11196	14.2	16.0	1.8	78	4E4	4.83	.23	8.10	11.60	186.0	1.10	1.48	32.70		19.70	34.18	.59
FAGU111	11197	16.4	17.6	1.2	100	4A4	3.16	.09	2.30	3.30	53.0	.62	.85	12.00		5.60	12.85	.59
FAGU111	11198	23.7	24.3	.6	100	4A4		.06	2.30	3.00	41.0					5.30		.57
FAGU111	11199	59.8	60.3	.5	100	4G4#	4.51	.12	8.40	10.00	134.0	1.58	1.69	20.50		18.40	22.19	.54
FAGU111	11200	60.3	61.6	1.3	92	4G48#	4.56	.21	3.60	2.90	48.0	1.71	4.76	34.90		6.50	39.66	.45
FAGU111	11201	61.6	62.9	1.3	100	4G48#	4.40	.08	5.40	7.10	94.0	.75	2.50	22.80		12.50	25.30	.57
FAGU111	11202	62.9	64.0	1.1	91	4G4	4.24	.07	3.50	5.40	60.0	.69	3.53	12.80		8.90	16.33	.61
FAGU111	11203	64.0	66.0	2.0	100	4CE8	3.65	.23	1.04	1.58	29.0	.89	4.20	17.30		2.62	21.50	.60
FAGU111	11204	66.0	67.4	1.4	100	4C38	3.58	.44	.54	.67	23.0	.48	5.90	19.30		1.21	25.20	.55
FAGU111	11205	67.4	68.2	.8	100	4C8	3.62	.24	.28	.38	13.0	.41	4.78	18.30		.66	23.08	.58
FAGU111	11206	68.2	69.3	1.1	100	4C8		.20	.29	.34	17.0					.63		.54
FAGU111	11207	69.3	70.1	.8	100	4D8	4.35	.17	2.50	3.60	38.0	.89	14.20	9.24		6.10	23.44	.59
FAGU111	11208	70.1	72.3	2.2	95	4C83	3.73	.38	.64	1.05	19.0	1.03	13.80	5.13		1.69	18.93	.62
FAGU111	11209	72.3	74.4	2.1	90	4C83		.30	.45	.73	16.0					1.18		.62
FAGU111	11210	74.4	76.5	2.1	100	4C83		.30	.74	.48	15.0					1.22		.39
FAGU111	11211	76.5	78.6	2.1	100	4C83		.15	.25	.48	9.0					.73		.66
FAGU111	11212	78.6	80.7	2.1	100	4C83		.27	.27	.32	9.0					.59		.54
FAGU111	11213	80.7	80.9	.2	100	4E8		.18	.12	.30	7.0					.42		.71
FAGU111	11214	80.9	83.4	2.5	96	4L1		.20	.24	.40	7.0					.64		.63
FAGU139	11215	37.9	39.8	1.9		4EG#	4.31	.16	7.20	7.30	107.0	.62	3.40	17.60		14.50	21.00	.50
FAGU139	11216	39.8	40.8	1.0		4E0	4.50	.20	1.06	2.50	30.0	2.13	4.25	36.40		3.56	40.65	.70
FAGU139	11217	40.8	42.7	1.9		4EG	4.67	.14	4.00	3.90	66.0	.89	2.50	32.50		7.90	35.00	.49
FAGU139	11219	44.2	45.5	1.3		4GC#	3.65	.06	8.70	7.60	113.0	.55	2.17	21.80		16.30	23.97	.47
FAGU139	11220	45.5	46.9	1.4		4L24	3.39	.20	1.26	1.25	20.0	.07	6.80	15.10		2.51	21.90	.50
FAGU139	11221	50.9	53.3	2.4		4LC#	3.39	.12	1.43	1.64	17.0	.14	5.60	12.90		3.07	18.50	.53
FAGU139	11222	53.3	56.7	3.4		4L24	3.50	.17	1.32	1.43	26.0	.14	7.50	14.70		2.75	22.20	.52
FAGU139	11223	64.7	66.7	2.0		4L245	3.77	.21	4.90	4.60	71.0	.34	5.60	17.10		9.50	22.70	.48
FAGU139	11224	66.7	68.9	2.2		4L245	3.67	.20	1.51	.84	25.0	.62	5.82	16.90		2.35	22.72	.36
FAGU088	11225	1.4	1.8	.4	100	4K4	4.54	.06	6.90	11.10	91.0	1.78	2.32	28.30		18.00	30.62	.62
FAGU088	11226	1.8	4.6	2.8	21	4E4*	4.57	.13	4.70	8.40	108.0	2.13	1.03	33.50		13.10	34.53	.64
FAGU115	11227	2.0	3.8	1.8	94	4DE4	3.81	.05	4.90	11.30	83.0	1.37	1.46	20.00		16.20	21.46	.70
FAGU088	11228	4.6	6.2	1.6	44	4E4	4.61	.06	1.69	4.20	41.0	1.51	.42	38.10		5.89	38.52	.71
FAGU088	11229	6.2	7.6	1.4	43	4D4	2.93	.10	6.10	15.30	119.0	1.51	1.38	13.90		21.40	15.28	.71
FAGU088	11230	7.6	8.8	1.2	67	4E4#	4.53	.15	4.10	7.90	94.0	2.95	.65	34.30		12.00	34.95	.66
FAGU088	11231	8.8	9.3	.5	100	4D4	4.03	.04	7.60	17.30	107.0	1.71	1.39	18.70		24.90	20.09	.69
FAGU088	11232	9.3	10.9	1.6	69	4E4	4.86	.09	6.10	9.40	94.0	2.74	1.25	33.40		15.50	34.65	.61
FAGU088	11233	10.9	12.6	1.7	53	4E4@	4.80	.18	6.10	7.00	107.0	1.99	1.29	35.00		13.10	36.29	.53
FAGU088	11234	12.6	14.3	1.7	41	4E4@	4.84	.21	7.70	12.20	133.0	2.61	1.50	30.30		19.90	31.80	.61
FAGU088	11235	14.3	15.6	1.3	54	4GE	4.78	.14	6.70	11.40	110.0	2.26	1.09	22.60		18.10	23.69	.63
FAGU088	11236	15.6	16.9	1.3	54	4AG	3.30	.08	1.88	3.10	39.0	1.30	.80	13.00		4.98	13.80	.62
FAGU088	11237	20.9	22.1	1.2	100	4L2		.06	.36	.33	12.0					.69		.48
FAGU088	11238	22.1	23.7	1.6	100	4AG		.07	1.23	1.83	26.0					3.06		.60
FAGU088	11239	50.4	51.8	1.4	93	4G4	4.60	.12	5.40	8.70	86.0	1.92	.60	10.50		14.10	11.10	.62
FAGU088	11240	51.8	53.4	1.6	88	4G4#	4.68	.10	6.70	8.60	111.0	1.10	.75	12.80		15.30	13.55	.56
FAGU088	11241	53.4	54.3	.9	89	4G4	4.54	.03	6.20	9.70	89.0	1.03	.42	7.67		15.90	8.09	.61
FAGU088	11242	54.3	54.6	.3	100	4G4#	4.56	.17	8.60	11.20	95.0	1.30	.85	15.50		19.80	16.35	.57
FAGU088	11243	56.2	57.0	.8	100	4G4#	4.21	.10	5.90	6.50	80.0	1.44	1.26	24.00		12.40	25.26	.52

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAO	PB+ZN	PC+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGU088	11244	57.0	57.5	.5	100	4G4*	4.58	.08	8.20	9.60	114.0	1.71	1.46	16.30		17.80	17.76	.54
FAGU088	11245	57.5	59.3	1.8	100	4E18#	4.54	.18	2.40	1.55	36.0	2.74	3.44	35.40		3.95	38.84	.39
FAGU088	11246	59.3	61.2	1.9	100	4E18#	4.56	.27	2.10	2.20	40.0	2.33	6.28	32.10		4.30	38.38	.51
FAGU088	11247	61.2	63.2	2.0	100	4G4#8	4.35	.11	5.00	6.20	80.0	.96	4.04	13.30		11.20	17.34	.55
FAGU088	11248	63.2	65.2	2.0	100	4G4#8	4.26	.09	2.60	5.50	44.0	.75	3.72	10.30		8.10	14.02	.68
FAGU115	11249	3.8	5.5	1.7	65	4DE4	3.77	.03	5.80	12.00	117.0	.55	1.17	12.80		17.80	13.97	.67
FAGU115	11250	5.5	8.5	3.0	20	4E4	4.70	.05	3.00	7.30	60.0	.69	1.12	31.60		10.30	32.72	.71
FAGU102	11251	39.2	41.1	1.9	100	4AE	3.79	.08	3.30	5.30	46.0	1.37	3.15	19.60		8.60	22.75	.62
FAGU102	11252	41.1	42.7	1.6	100	4E45	3.74	.11	3.10	7.80	53.0	1.85	3.35	17.20		10.90	20.55	.72
FAGU102	11253	42.7	44.2	1.5	100	4E45	4.10	.29	4.00	7.10	66.0	1.92	3.25	21.70		11.10	24.95	.64
FAGU102	11254	44.2	45.7	1.5	100	4E45	3.69	.25	2.80	5.80	46.0	1.51	4.16	17.30		8.60	21.46	.67
FAGU108	11255	10.9	12.8	1.9	100	4A0	3.10	.12	.63	1.37	21.0	.69	1.40	11.50		2.00	12.90	.69
FAGU108	11256	54.5	55.9	1.4	100	4G4#	4.66	.03	7.10	9.50	113.0	.48	1.20	17.10		16.60	18.30	.57
FAGU108	11257	55.9	57.9	2.0	90	4E4#	4.29	.09	6.50	8.30	103.0	.55	1.55	16.90		14.80	18.45	.56
FAGU108	11258	57.9	59.5	1.6	31	4E4#	4.43	.10	5.40	8.30	94.0	.55	1.30	16.30		13.70	17.60	.61
FAGU108	11259	59.5	60.6	1.1	64	4E4#	4.40	.09	5.70	8.30	95.0	.75	3.30	27.10		14.00	30.40	.59
FAGU108	11260	60.6	61.6	1.0	90	4D4	3.86	.12	6.20	7.00	88.0	.82	5.74	17.70		13.20	23.44	.53
FAGU108	11261	61.6	64.0	2.4	92	4C3	3.72	.16	.89	1.27	24.0	1.45	3.89	22.30		2.16	26.19	.59
FAGU108	11262	64.0	64.5	.5	100	4D4	3.67	.10	4.30	5.80	58.0	1.44	3.00	16.80		10.10	19.80	.57
FAGU108	11263	64.5	65.0	.5	100	4A14	3.77	.10	3.40	3.60	37.0	1.78	2.03	18.10		7.00	20.13	.51
FAGU108	11264	65.0	66.5	1.5	100	4A13	3.74	.24	1.35	1.35	27.0	2.54	1.79	24.50		2.70	26.29	.50
FAGU108	11265	66.5	68.9	2.4	58	4C3	3.79	.30	.99	1.40	26.0	1.17	1.63	24.00		2.39	25.63	.59
FAGU108	11266	68.9	70.5	1.6	69	4E1		.30	.17	.60	13.0					.77		.78
FAGU108	11267	70.5	72.1	1.6	87	4E1		.38	.43	.77	18.0					1.20		.64
FAGA159	11268	102.7	103.5	.8	100	4E#4	4.67	.19	4.30	1.88	58.0	2.88	3.69	35.20		6.18	38.89	.30
FAGA159	11269	103.5	104.5	1.0	100	4A3	3.74	.17	.68	.98	23.0	1.30	2.17	21.10		1.66	23.27	.59
FAGA159	11270	104.5	105.2	.7	100	4E#4	4.23	.19	4.00	4.80	67.0	1.17	3.00	24.20		8.80	27.20	.55
FAGA159	11271	107.0	107.5	.5	80	5A1	3.33	.08	.80	.79	18.0	.21	5.30	11.30		1.59	16.60	.50
FAGA159	11272	107.5	107.8	.3	100	4E*4	4.24	.19	3.30	4.00	54.0	1.03	3.65	27.30		7.30	30.95	.55
FAGA159	11273	107.8	108.5	.7	86	4E*	3.92	.15	2.40	2.10	37.0	1.17	2.55	23.70		4.50	26.25	.47
FAGA159	11274	108.5	109.2	.7	100	4C*	3.67	.11	2.20	1.92	28.0	.69	4.92	15.20		4.12	20.12	.47
FAGA159	11275	109.2	111.4	2.2	100	4E#8	4.83	.29	2.30	1.92	37.0	1.23	3.65	32.20		4.22	35.85	.45
FAGA159	11276	111.4	111.8	.4	100	4E*4	4.81	.19	5.70	7.40	104.0	1.51	1.52	31.40		13.10	32.92	.56
FAGA159	11277	111.8	112.3	.5	100	4C0	3.45	.14	1.32	1.43	30.0	.34	7.50	10.00		2.75	17.50	.52
FAGU104	11278	.0	2.3	2.3	96	4ED4	4.61	.17	7.50	15.60	114.0	1.65	1.50	24.50		23.10	26.00	.68
FAGU104	11279	2.3	4.6	2.3	78	4ED4	3.84	.05	7.40	15.20	112.0	1.17	2.03	12.70		22.60	14.73	.67
FAGU104	11280	4.6	6.9	2.3	61	4ED4	4.28	.04	7.40	16.20	103.0	1.44	1.43	17.20		23.60	18.63	.69
FAGU104	11281	6.9	9.2	2.3	100	4ED4	4.61	.13	10.60	19.00	154.0	1.65	2.13	18.30		29.60	20.43	.64
FAGU104	11282	9.2	11.5	2.3	100	4ED4	4.45	.04	11.80	19.90	166.0	1.37	2.08	15.50		31.70	17.58	.63
FAGU104	11283	11.5	13.7	2.2	68	4ED4	4.26	.17	7.80	14.00	133.0	1.03	2.17	20.70		21.80	22.87	.64
FAGU113	11284	62.2	63.0	.8	50	4E0	3.35	.02	1.27	3.20	29.0	.48	3.81	9.40		4.47	13.21	.72
FAGU113	11285	63.0	63.8	.8	87	4D0	3.25	.04	3.70	5.30	50.0	.41	2.31	8.00		9.00	10.31	.59
FAGU113	11286	63.8	65.2	1.4	86	4E4#	3.69	.02	5.60	4.50	77.0	.82	2.25	14.50		10.10	16.75	.45
FAGU113	11287	65.2	66.1	.9	100	4E4#	4.61	.10	9.90	6.40	118.0	1.23	2.14	26.20		16.30	28.34	.39
FAGU113	11288	69.9	70.4	.5	100	4G4#	4.42	.03	5.40	9.00	74.0	.34	1.35	12.00		14.40	13.35	.63
FAGU113	11289	73.7	74.7	1.0	100	4E48*	3.56	.13	4.80	4.10	69.0	.41	5.04	12.10		8.90	17.14	.46
FAGU113	11290	74.7	76.1	1.4	100	4G487	4.56	.08	12.60	7.30	142.0	.75	13.50	13.10		19.90	26.60	.37
FAGU113	11291	76.1	77.5	1.4	93	4G487	4.42	.12	9.20	8.50	109.0	.82	10.10	11.50		17.70	21.60	.48
FAGU113	11292	77.5	78.0	.5	100	4H4@	4.63	.36	13.50	6.80	134.0	.62	21.50	8.60		20.30	30.10	.33
FAGU113	11293	78.0	79.7	1.7	100	4E84	4.70	.13	2.80	2.80	39.0	.96	7.43	33.00		5.60	40.43	.50

DDH	SAMPLE	---DEPTHS---	INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PG	PY	BAC	PB+ZN	PC+PY	ZN
		FROM TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGU113	11294	79.7 81.5	1.8	100	4E84	4.29	.28	2.80	3.60	43.0	.89	5.60	26.00		6.40	31.60	.56
FAGU113	11295	81.5 83.2	1.7	59	4E84	4.72	.23	5.10	5.30	65.0	1.44	3.83	30.40		10.40	34.23	.51
FAGU113	11296	83.2 84.9	1.7	100	4E84	4.53	.21	4.50	5.60	64.0	1.03	3.83	28.40		10.10	32.23	.55
FAGU113	11297	84.9 86.3	1.4	100	4G4#	4.35	.05	4.70	8.70	72.0	.34	1.71	15.50		13.40	17.21	.65
FAGU113	11298	86.3 87.7	1.4	100	4G4#	4.43	.04	3.30	8.00	60.0	.14	1.66	8.00		11.30	9.66	.71
FAGU113	11299	87.7 88.2	.5	100	4E4*	4.35	.04	3.40	5.70	54.0	.34	6.40	16.40		9.10	22.80	.63
FAGU113	1130C	88.2 89.5	1.3	85	4C87*	3.51	.12	1.76	2.10	30.0	.34	7.70	14.90		3.86	22.60	.54
FAGU092	11301	28.4 29.9	1.5	100	4EC	4.08	.24	2.50	3.00	52.0	3.29	1.55	28.70		5.50	30.25	.55
FAGUC92	11302	29.9 31.4	1.5	100	4EC	3.89	.18	.93	2.90	32.0	2.67	1.92	26.90		3.83	28.82	.76
FAGU092	11303	31.4 32.8	1.4	100	4AE	3.59	.14	2.00	4.00	43.0	1.71	1.54	19.80		6.00	21.34	.67
FAGU092	11304	32.8 34.3	1.5	100	4AE	3.82	.13	.40	1.31	16.0	1.37	2.43	27.30		1.71	29.73	.77
FAGUC92	11305	34.3 35.9	1.6	100	4AE4	3.94	.21	2.30	4.10	43.0	2.33	1.93	24.90		6.40	26.83	.64
FAGU092	11306	35.9 37.5	1.6	100	4AE4	3.82	.20	3.40	5.90	56.0	2.26	2.34	21.30		9.30	23.64	.63
FAGU092	11307	37.5 39.6	2.1	100	4E14	3.82	.20	2.30	3.30	50.0	2.61	1.99	23.90		5.60	25.89	.59
FAGU092	11308	39.6 41.7	2.1	100	4E14	3.68	.10	2.40	2.90	46.0	1.44	1.65	21.60		5.30	23.25	.55
FAGU092	11309	41.7 42.7	1.0	90	4A34	3.65	.06	1.62	2.90	35.0	.96	1.70	21.00		4.52	22.70	.64
FAGUC92	1131C	42.7 44.0	1.3	92	4AC3	3.67	.08	.71	1.64	24.0	1.30	2.43	23.50		2.35	25.93	.70
FAGU092	11311	44.0 45.4	1.4	86	4AC3	3.82	.10	.86	3.50	32.0	1.30	2.85	26.20		4.36	29.05	.80
FAGUC92	11312	45.4 46.6	1.2	83	4B4	2.95	.01	2.70	6.00	34.0	.41	1.66	2.47		8.70	4.13	.69
FAGU092	11313	46.6 47.7	1.1	91	4B4	2.99	.02	4.00	5.20	50.0	.55	1.35	2.06		9.20	3.41	.57
FAGU125	11314	.0 1.5	1.5	33	4E4	4.49	.23	13.20	26.80	141.0	2.06	1.22	15.80		40.00	17.02	.67
FAGU125	11315	1.5 3.9	2.4	75	4EK	4.70	.18	6.50	11.40	113.0	1.58	2.39	30.30		17.90	32.69	.64
FAGU125	11316	3.9 7.0	3.1	52	4EK	4.69	.14	4.70	8.30	95.0	1.37	3.03	32.50		13.00	35.53	.64
FAGU125	11317	7.0 10.0	3.0	70	4EK	4.94	.16	5.00	8.60	110.0	1.51	2.88	22.90		13.60	25.78	.63
FAGU125	11318	10.0 12.5	2.5	52	4E4	4.93	.06	5.50	12.20	92.0	1.17	2.83	30.50		17.70	33.33	.69
FAGU125	11319	12.5 14.6	2.1	48	4D4	3.92	.05	4.60	11.50	83.0	.69	2.88	19.10		16.10	21.98	.71
FAGU125	1132C	14.6 16.2	1.6	94	4D4	3.74	.03	7.60	17.70	133.0	.89	2.15	8.10		25.30	10.25	.70
FAGU125	11321	16.2 18.2	2.0	100	4D4	3.69	.18	8.80	16.40	160.0	1.58	2.59	9.50		25.20	12.09	.65
FAGU125	11322	18.2 20.4	2.2	100	4D4	3.90	.04	8.60	23.00	153.0	1.51	2.02	9.50		31.60	11.52	.73
FAGU125	11323	20.4 22.1	1.7	88	4D4	4.07	.03	10.00	25.40	166.0	1.03	3.41	8.40		35.40	11.81	.72
FAGU125	11324	22.1 23.3	1.2	50	4D4	4.03	.20	10.40	17.50	169.0	1.65	2.93	13.00		27.90	15.93	.63
FAGU125	11325	23.3 25.3	2.0	85	4D41	4.64	.03	3.30	8.70	54.0	.75	4.23	30.10		12.00	34.33	.72
FAGU125	11326	25.3 28.2	2.9	86	4EL	4.04	.11	6.70	15.70	121.0	1.23	2.64	13.70		22.40	16.34	.70
FAGU125	11327	28.2 30.4	2.2	95	4EKD	4.80	.10	6.00	12.90	120.0	.89	3.41	24.60		18.90	28.01	.68
FAGU125	11328	30.4 32.8	2.4	96	4DA4	3.82	.06	9.40	17.50	168.0	1.30	2.64	11.30		26.90	13.94	.65
FAGU125	11329	32.8 34.2	1.4	100	4DA4	3.96	.06	10.60	20.60	185.0	1.17	2.44	11.90		31.20	14.34	.66
FAGU125	1133C	34.2 36.0	1.8	72	4ED4	4.28	.06	5.20	12.00	100.0	.69	2.83	23.00		17.20	25.83	.70
FAGU125	11331	36.0 37.0	1.0	60	4D12	3.64	.03	3.00	7.20	48.0	.48	2.73	16.80		10.20	19.53	.71
FAGU125	11332	37.0 38.5	1.5	100	4E4#	4.88	.15	5.30	8.90	70.0	1.92	2.83	34.30		14.20	37.13	.63
FAGU125	11333	38.5 39.7	1.2	100	4E4#	4.83	.20	6.10	9.80	92.0	1.10	2.44	32.50		15.90	34.94	.62
FAGU125	11334	39.7 40.7	1.0	100	4CD4	3.68	.09	3.80	7.70	77.0	.69	1.43	16.30		11.50	17.73	.67
FAGU125	11335	40.7 42.1	1.4	86	4ED4	4.42	.07	5.10	10.70	88.0	1.10	1.38	25.50		15.80	26.88	.68
FAGU125	11336	42.1 44.7	2.6	100	5B69	3.04	.06	.56	1.56	8.0	.21	1.92	4.61		2.12	6.53	.74
FAGU125	11337	52.2 54.2	2.0		4E4#	4.06	.18	6.40	11.10	114.0	1.65	1.82	20.80		17.50	22.62	.63
FAGU125	11338	54.2 56.2	2.0		4E4#	4.63	.13	5.30	9.90	97.0	1.58	2.86	28.80		15.20	31.66	.65
FAGU125	11339	56.2 58.2	2.0		4E4#	4.98	.22	5.10	7.60	91.0	1.51	2.81	33.70		12.70	36.51	.60
FAGU125	1134C	58.2 60.2	2.0		4E4#	4.94	.15	5.80	8.30	98.0	1.44	2.77	33.30		14.10	36.07	.59
FAGU125	11341	60.2 61.2	1.0		4E4#	4.86	.22	6.50	12.00	125.0	5.62	3.00	29.70		18.50	32.70	.65
FAGU125	11342	61.2 61.9	.7		4A4	3.33	.08	5.60	8.50	82.0	1.23	1.91	7.20		14.10	9.11	.60
FAGU125	11343	61.9 64.0	2.1		4A0	3.31	.11	1.40	2.32	31.0	.75	1.64	14.30		3.72	15.94	.62

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	FY	BAO	PB+ZN	PC+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGU125	11344	64.0	66.0	2.0		4A0	3.19	.10	1.68	3.00	34.0	1.03	1.87	11.40		4.68	13.27	.64
FAGU125	11345	66.0	68.0	2.0		4A0	3.29	.14	.37	1.02	20.0	.69	1.92	15.20		1.39	17.12	.73
FAGU125	11346	68.0	70.0	2.0		4A0	3.20	.12	.54	.86	21.0	.41	1.76	12.90		1.40	14.66	.61
FAGU125	11347	70.0	72.4	2.4		4A0	3.10	.10	.40	.86	16.0	.31	1.82	10.10		1.26	11.92	.68
FAGU125	11348	72.4	75.0	2.6		4ECA	3.91	.18	5.30	10.60	100.0	1.65	2.95	19.20		15.90	22.15	.67
FAGU125	11349	75.0	77.0	2.0	75	4E4	4.78	.17	3.10	7.10	52.0	1.37	4.27	31.60		10.20	35.87	.70
FAGU125	11350	77.0	78.5	1.5	100	4E4	4.76	.10	2.40	4.90	43.0	1.51	3.14	34.60		7.30	37.74	.67
FAGU125	11351	78.5	80.5	2.0	100	4D4	4.04	.10	6.10	17.50	114.0	1.23	3.00	14.80		23.60	17.80	.74
FAGU125	11352	80.5	83.4	2.9	100	4D4	3.99	.06	10.20	20.60	182.0	1.65	2.74	11.40		30.80	14.14	.67
FAGU125	11353	83.4	84.7	1.3	100	4D41	3.41	.01	1.90	6.50	27.0	.55	3.56	10.20		8.40	13.76	.77
FAGU125	11354	84.7	86.6	1.9	100	4D4	3.79	.07	4.50	13.70	116.0	1.03	2.76	14.10		18.20	16.86	.75
FAGU125	11355	86.6	89.0	2.4	100	4D4	3.69	.14	7.90	18.20	138.0	1.37	2.58	8.50		26.10	11.08	.70
FAGU125	11356	89.0	90.7	1.7	82	4D4	3.71	.03	8.60	20.50	140.0	1.03	3.91	6.50		29.10	10.41	.70
FAGU125	11357	90.7	92.3	1.6	100	4A4	3.47	.25	3.30	2.40	52.0	1.65	1.48	16.50		5.70	17.98	.42
FAGU100	11358	.0	3.0	3.0	47	4E4	4.75	.14	6.10	11.60	121.0	1.65	2.54	28.80		17.70	31.34	.66
FAGU100	11359	3.0	6.1	3.1	68	4D45	4.08	.06	9.00	17.60	137.0	1.23	2.28	15.60		26.60	17.88	.66
FAGU100	11360	6.1	7.6	1.5	100	4D45	4.17	.03	8.20	15.90	132.0	1.65	1.92	12.20		24.10	14.12	.66
FAGU100	11361	7.6	9.1	1.5	100	4D45	3.73	.04	6.50	13.50	101.0	1.58	1.20	12.50		20.00	13.70	.68
FAGU100	11362	9.1	10.7	1.6	100	4D45	4.05	.05	5.90	11.60	98.0	2.06	2.08	17.30		17.50	19.38	.66
FAGU100	11363	10.7	12.2	1.5	93	4D45	3.84	.07	3.10	6.50	49.0	1.65	3.61	16.70		9.60	20.31	.68
FAGU100	11364	12.2	13.5	1.3	100	4D45	3.65	.08	5.50	9.80	81.0	1.37	2.63	13.40		15.30	16.03	.64
FAGU100	11365	13.5	15.2	1.7	100	4E45	4.05	.07	2.40	6.50	42.0	1.92	3.04	25.60		8.90	28.64	.73
FAGU100	11366	15.2	17.8	2.6	38	4ED	4.53	.27	.89	4.80	30.0	1.78	4.19	30.80		5.69	34.99	.84
FAGU100	11367	17.8	19.8	2.0	80	4AD	3.84	.13	2.60	4.30	44.0	1.85	1.57	22.20		6.90	23.77	.62
FAGU100	11368	19.8	22.0	2.2	55	4ED	4.11	.12	1.87	4.80	39.0	1.71	1.87	25.60		6.67	27.47	.72
FAGU100	11369	22.0	24.4	2.4	100	4A4	3.65	.07	1.77	2.70	33.0	1.17	1.40	15.00		4.47	16.40	.60
FAGU100	11371	25.9	27.4	1.5	100	4A4	3.59	.04	1.71	3.90	31.0	.96	1.76	16.50		5.61	18.26	.70
FAGU100	11372	27.4	29.0	1.6	100	4A4	3.43	.03	1.22	2.60	23.0	1.10	1.33	13.90		3.82	15.23	.68
FAGU100	11373	29.0	30.5	1.5	100	4A4	3.69	.07	1.91	4.80	37.0	.96	1.76	18.20		6.71	19.96	.72
FAGU100	11374	30.5	32.0	1.5	100	4A4	3.35	.05	3.30	6.20	54.0	.89	1.76	10.80		9.50	12.56	.65
FAGU100	11375	32.0	33.5	1.5	100	4A4	3.01	.02	3.20	5.20	32.0	.41	.96	1.05		8.40	2.01	.62
FAGU100	11376	33.5	36.0	2.5	60	4A4	2.92	.01	1.53	3.40	24.0	.41	.76	.80		4.93	1.56	.69
FAGU100	11377	36.0	37.8	1.8	56	4A4	2.93	.03	1.04	3.30	16.0	.21	.81	1.43		4.34	2.24	.76
FAGU100	11378	37.8	39.6	1.8	72	4A4	3.19	.03	2.30	6.10	36.0	.48	1.96	5.80		8.40	7.76	.73
FAGU100	11379	39.6	44.2	4.6	46	4DA	3.04	.05	3.30	8.40	63.0	.34	1.47	1.50		11.70	2.97	.72
FAGU100	11380	44.2	47.2	3.0	43	4A4	2.99	.10	2.40	3.70	44.0	.62	.96	3.66		6.10	4.62	.61
FAGU100	11381	47.2	53.3	6.1	49	4A4	3.20	.12	3.00	2.50	51.0	1.10	1.25	8.80		5.50	10.05	.45
FAGU100	11382	53.3	56.5	3.2	88	4L2	3.04	.02	.16	.19	6.0	1.03	2.92	3.40		.35	6.32	.54
FAGU100	11383	56.5	58.7	2.2	95	4A0	3.01	.03	.94	2.30	20.0	.41	2.75	3.19		3.24	5.94	.71
FAGU100	11385	82.1	82.8	.7	100	4L4	2.96	.05	1.28	3.40	28.0	.34	1.40	2.44		4.68	3.84	.73
FAGU100	11386	82.8	89.7	6.9	58	5D4*	3.10	.03	.54	1.83	13.0	.55	4.86	3.46		2.37	8.32	.77
FAGU100	11387	89.7	90.4	.7	100	4A4	3.14	.03	2.04	4.00	35.0	.69	.87	7.20		6.04	8.07	.66
FAGU100	11388	90.4	92.6	2.2	45	4EA4	4.23	.09	3.00	6.00	60.0	.96	1.69	23.50		9.00	25.19	.67
FAGU102	11389	.0	1.9	1.9	32	4D435	4.53	.09	9.10	16.70	147.0	1.99	2.16	20.20		25.80	22.36	.65
FAGU102	11390	1.9	4.0	2.1	100	4DE4	3.93	.03	7.60	15.80	133.0	1.65	1.82	14.50		23.40	16.32	.68
FAGU102	11391	4.0	6.1	2.1	71	4DE4	4.08	.04	7.90	17.00	134.0	1.78	1.62	17.20		24.90	18.82	.68
FAGU102	11392	6.1	8.1	2.0	75	4DE4	4.23	.09	9.40	18.30	132.0	1.78	1.82	16.00		27.70	17.82	.66
FAGU102	11393	8.1	12.1	4.0	38	4EL	3.18	.07	1.37	2.50	26.0	.69	3.46	6.50		3.87	9.96	.65
FAGU102	11394	12.1	13.7	1.6	94	4D435	3.87	.07	4.50	7.10	65.0	1.51	1.96	20.60		11.60	22.56	.61
FAGU102	11395	13.7	15.2	1.5	80	4D435	3.80	.05	3.70	8.20	61.0	1.44	1.55	17.10		11.90	18.65	.69

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAO	PB+ZN	PC+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGU102	11396	15.2	17.9	2.7	26	5B62	3.10	.02	.35	1.14	9.0	.27	5.01	2.55		1.49	7.56	.77
FAGU102	11397	17.9	19.8	1.9	74	4D435	3.62	.06	4.70	4.70	67.0	.69	7.14	13.50		9.40	20.64	.50
FAGU102	11398	19.8	21.3	1.5	20	5B6	3.04	.04	.33	.61	10.0	.27	2.75	3.86		.94	6.61	.65
FAGU102	11399	21.3	21.7	.4	100	4E4	4.31	.11	6.50	12.00	132.0	1.44	1.55	23.40		18.50	24.95	.65
FAGU102	11400	21.7	27.4	5.7	49	4A0	3.33	.11	.89	1.78	21.0	.55	3.83	9.60		2.67	13.43	.67
FAGU096	11401	1.0	3.0	2.0	50	4E4#	5.36	.21	5.30	12.20	105.0	2.26	2.09	31.90		17.50	33.99	.70
FAGU096	11402	3.0	4.6	1.6	19	4E4#	5.03	.06	4.10	12.90	52.0	.96	1.25	34.00		17.00	35.25	.76
FAGU096	11403	4.6	6.0	1.4	86	4E4#	4.91	.11	4.50	15.10	64.0	1.51	2.16	29.60		19.60	31.76	.77
FAGU096	11404	6.0	7.4	1.4	57	4E4#	5.03	.12	3.90	12.10	73.0	1.51	2.59	33.20		16.00	35.79	.76
FAGU096	11405	7.4	9.3	1.9	100	4D4	4.25	.07	8.50	16.20	126.0	1.65	2.23	16.70		24.70	18.93	.66
FAGU096	11406	9.3	10.4	1.1	100	4E4#	5.01	.26	6.20	13.70	105.0	2.47	1.18	28.10		19.90	29.28	.69
FAGU096	11407	10.4	11.2	.8	100	4D34#	4.01	.02	7.50	15.80	117.0	1.37	1.55	15.00		23.30	16.55	.68
FAGU096	11408	11.2	13.0	1.8	100	4A34#	4.42	.06	7.10	12.90	108.0	2.26	1.81	19.20		20.00	21.01	.65
FAGU096	11409	13.0	14.8	1.8	100	4A34#	3.73	.03	4.30	11.10	70.0	1.44	2.24	9.90		15.40	12.14	.72
FAGU096	11410	14.8	16.7	1.9	100	4A34#	3.66	.05	5.50	11.20	90.0	2.06	2.18	14.30		16.70	16.48	.67
FAGU096	11411	16.7	18.6	1.9	100	4KE	5.03	.09	.61	4.30	22.0	2.26	4.42	36.50		4.91	40.92	.88
FAGU096	11412	18.6	19.3	.7	100	4A14	3.89	.14	1.82	5.10	48.0	2.13	1.99	19.90		6.92	21.89	.74
FAGU096	11413	19.3	20.0	.7	100	4EA	4.99	.11	.95	2.80	23.0	2.13	1.10	31.80		3.75	32.90	.75
FAGU096	11414	20.0	20.3	.3	100	4E0	3.84	.08	1.72	2.70	32.0	1.51	1.18	26.60		4.42	27.78	.61
FAGU096	11415	20.3	21.5	1.2	100	4AC3	3.85	.09	.85	2.50	24.0	1.71	1.55	26.40		3.35	27.95	.75
FAGU096	11416	21.5	22.7	1.2	92	4AC3	3.77	.04	.97	3.30	25.0	.89	1.68	15.50		4.27	17.18	.77
FAGU096	11417	22.7	24.4	1.7	100	4A1	3.02	.02	.42	.88	13.0	.48	1.10	6.50		1.30	7.60	.68
FAGU096	11418	24.4	26.1	1.7	100	4A1	3.12	.03	1.18	3.20	23.0	.69	1.33	7.80		4.38	9.13	.73
FAGU096	11419	26.1	28.1	2.0	100	4E0	3.96	.11	2.90	5.50	48.0	1.92	1.62	24.20		8.40	25.82	.65
FAGU096	11420	28.1	30.4	2.3	96	4A134	3.61	.10	3.30	3.90	48.0	1.65	.86	18.80		7.20	19.66	.54
FAGU096	11421	30.4	31.5	1.1	100	4A3	3.99	.12	1.01	.95	25.0	1.78	1.68	25.20		1.96	26.88	.48
FAGU096	11422	31.5	32.2	.7	86	4E1	3.85	.10	2.40	3.00	39.0	1.44	1.62	23.80		5.40	25.42	.56
FAGU096	11423	32.2	33.7	1.5	100	4A10	2.93	.02	1.26	3.30	19.0	.34	1.40	1.66		4.56	3.06	.72
FAGU096	11424	33.7	35.3	1.6	94	4A14	2.90	.01	1.89	3.70	29.0	.41	.67	.82		5.59	1.49	.66
FAGU096	11425	35.3	36.2	.9	89	5C4*	3.01		.49	.93	11.0	.14	3.61	3.12		1.42	6.73	.65
FAGU096	11426	36.2	37.7	1.5	100	4L14	3.02		1.93	3.90	34.0	.48	1.40	2.29		5.83	3.69	.67
FAGU096	11427	39.2	40.4	1.2	75	4L3	2.99		1.72	3.30	36.0	.48	2.24	5.20		5.02	7.44	.66
FAGU096	11428	40.4	41.7	1.3	46	4L3	2.92		.56	.47	12.0	.34	2.18	4.64		1.03	6.82	.46
FAGU096	11429	41.7	43.5	1.8	39	4A10	3.00		1.01	1.86	22.0	.41	1.38	4.80		2.87	6.18	.65
FAGU096	11430	43.5	45.4	1.9	42	4A1	2.92		1.31	2.30	35.0	.48	1.99	4.36		3.61	6.35	.64
FAGU096	11431	45.4	47.3	1.9	63	4A10	2.90		.66	1.09	17.0	.14	2.72	2.97		1.75	5.69	.62
FAGU096	11432	47.3	48.8	1.5	53	4A31	3.28		1.42	3.20	34.0	.69	2.12	13.60		4.62	15.72	.69
FAGU096	11433	48.8	50.3	1.5	53	4A31	3.02		.60	1.62	16.0	.27	3.61	6.60		2.22	10.21	.73
FAGU096	11434	50.3	51.8	1.5	40	4A31	2.85		1.38	1.65	19.0	.27	1.99	1.76		3.03	3.75	.54
FAGU096	11435	53.2	56.4	3.2	19	4A1	2.88		1.29	1.86	22.0	.21	2.72	1.15		3.15	3.87	.59
FAGU096	11436	56.4	57.9	1.5	80	5B96	2.85		.50	1.52	11.0	.21	1.25	.97		2.02	2.22	.75
FAGU096	11437	57.9	59.5	1.6	100	5B96	2.91		.55	1.13	12.0	.34	1.55	1.27		1.68	2.82	.67
FAGU096	11438	59.5	61.2	1.7	59	5B96	2.93		.21	.36	10.0	.14	5.00	1.62		.57	6.62	.63
FAGU096	11439	97.9	99.0	1.1	64	4A143	3.42		3.30	2.40	48.0	.69	1.25	15.30		5.70	16.55	.42
FAGU096	11440	99.0	99.8	.8	87	4A4	3.47		3.70	7.87	51.0	1.10	2.21	9.40		11.57	11.61	.68
FAGU096	11441	99.8	101.7	1.9	53	4E4	4.45		8.30	16.00	139.0	1.10	.71	25.50		24.30	26.21	.66
FAGU096	11442	101.7	103.7	2.0	100	4E4	4.42		8.10	17.70	122.0	.89	1.47	22.10		25.80	23.57	.69
FAGU096	11443	103.7	104.0	.3	100	4E4	3.78		7.70	16.70	130.0	1.20	2.43	12.70		24.40	15.13	.68
FAGU096	11444	37.7	39.2	1.5	100	4L14	3.03		2.90	6.30	47.0	.48	2.10	3.70		9.20	5.80	.68
FAGU108	11445	.0	3.0	3.0	37	4D4	3.74		9.00	20.20	136.0	.69	1.65	8.90		29.20	10.55	.69

DDH	SAMPLE	---DEPTHS---	INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	SAO	PB+ZN	PO+PY	ZN
		FROM TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGU108	11446	3.0 4.6	1.6	44	4E4*	4.86	.05	2.90	6.50	50.0	1.03	.81	37.30		9.40	38.11	.69
FAGU108	11447	4.6 6.1	1.5	53	4E4*	4.82	.20	3.90	6.60	110.0	2.06	.74	34.50		10.50	35.24	.63
FAGU108	11448	6.1 8.7	2.6	42	4E4*	4.80	.10	7.60	14.20	127.0	1.78	1.08	27.20		21.80	28.28	.65
FAGU108	11449	8.7 9.0	.3	67	4A0	3.68	.09	1.19	1.59	32.0	1.03	1.41	22.90		2.78	24.31	.57
FAGU108	11450	9.0 10.9	1.9	100	4A0	3.33	.10	.91	1.71	24.0	.69	1.54	13.20		2.62	14.74	.65
FAGU113	11451	89.5 90.8	1.3	100	4C87*	3.76	.17	.98	1.93	26.0	1.10	7.39	20.20		2.91	27.59	.66
FAGU113	11452	90.8 93.3	2.5	100	4C78*	3.65	.23	.41	.52	15.0	.69	6.80	16.50		.93	23.30	.56
FAGA100	11453	65.4 66.2	.8	100	4G4#	4.50	.06	10.30	11.30	190.0	.96	1.82	19.40		21.60	21.22	.52
FAGA100	11454	67.4 68.7	1.3	100	4G4#	4.35	.03	10.50	12.60	183.0	1.03	1.76	19.50		23.10	21.26	.55
FAGA100	11455	68.7 70.1	1.4	64	4K4	3.65	.02	3.50	5.40	52.0	.41	1.88	14.70		8.90	16.58	.61
FAGA100	11456	71.1 72.1	1.0	100	4G4#	4.45	.03	12.90	13.50	195.0	.69	1.14	20.50		26.40	21.64	.51
FAGA100	11457	72.1 72.5	.4	100	4K4#	3.62	.06	4.20	6.60	86.0	.69	1.88	13.70		10.80	15.58	.61
FAGA100	11458	72.5 73.5	1.0	90	4G4#	4.31	.12	11.10	11.50	184.0	1.71	1.94	18.40		22.60	20.34	.51
FAGA100	11459	81.3 82.7	1.4	50	4G4#	4.37	.05	5.90	8.70	99.0	.69	2.38	15.90		14.60	18.28	.60
FAGA100	11460	88.8 89.6	.8	62	4DG#	4.13	.06	9.00	8.30	131.0	.27	1.88	12.60		17.30	14.48	.48
FAGA100	11461	90.9 91.4	.5	100	4G4#	4.21	.07	7.00	9.10	114.0	.69	4.44	9.10		16.10	13.54	.57
FAGA100	11462	91.4 92.1	.7	100	4E4*	4.69	.08	9.40	8.40	132.0	1.65	1.22	24.90		17.80	26.12	.47
FAGA100	11463	92.1 93.5	1.4	93	4D0	3.96	.15	3.10	3.60	50.0	1.17	2.49	17.10		6.70	19.59	.54
FAGA100	11464	93.5 94.1	.6	100	4L14	3.04	.05	.45	.73	9.0	.21	2.62	3.39		1.18	6.01	.62
FAGA100	11465	174.7 176.5	1.8	56	4G4#	4.19	.03	6.40	10.80	103.0	.27	1.01	19.50		17.20	20.51	.63
FAGA100	11466	176.5 178.3	1.8	100	4G4#	4.70	.11	7.00	10.70	119.0	.62	.87	13.60		17.70	14.47	.60
FAGA100	11467	178.3 180.0	1.7	82	4E41	4.86	.08	2.80	4.40	53.0	1.03	1.59	35.00		7.20	36.59	.61
FAGA100	11468	180.0 181.7	1.7	82	4E41	4.81	.09	3.90	5.90	66.0	1.03	1.94	34.30		9.80	36.24	.60
FAGA100	11469	181.7 184.1	2.4	50	4A4	3.35	.06	3.40	6.10	54.0	.96	1.35	11.20		9.50	12.55	.64
FAGA100	11470	184.1 185.0	.9	56	4A4	3.09	.04	2.50	4.00	45.0	.55	1.88	4.86		6.50	6.74	.62
FAGA100	11471	185.0 185.4	.4	100	4A4	3.23	.03	4.70	7.40	76.0	.48	2.10	3.39		12.10	5.49	.61
FAGA100	11472	185.4 187.2	1.8	89	4A0	3.00	.02	.37	.69	7.0	.27	2.23	2.54		1.06	4.77	.65
FAGA100	11473	187.2 189.0	1.8	94	4A0	3.04	.03	.36	.31	7.0	.07	3.21	3.24		.67	6.45	.46
FAGUG67	11474	.0 3.1	3.1	65	4A0	3.10	.09	1.57	1.53	25.0	.82	1.60	9.30		3.10	10.90	.49
FAGUG67	11475	3.1 5.4	2.3	87	4A0	3.11	.07	1.67	1.78	24.0	.89	1.44	8.78		3.45	10.22	.52
FAGUG67	11476	5.4 7.6	2.2	91	4AE	3.04	.03	2.60	4.60	34.0	.75	1.57	6.11		7.20	7.68	.64
FAGUG67	11477	7.6 9.2	1.6	69	4A14	3.12	.03	4.30	5.00	48.0	.82	1.44	15.90		9.30	17.34	.54
FAGUG67	11478	9.2 10.8	1.6	100	4A14	2.96	.04	2.90	4.00	37.0	1.23	1.27	3.68		6.90	4.95	.58
FAGUG67	11479	10.8 12.1	1.3	100	4E05	3.87	.03	.73	1.93	23.0	.82	1.07	28.50		2.66	29.57	.73
FAGUG67	11480	12.1 13.5	1.4	100	4AE	4.27	.03	.48	1.85	15.0	.55	1.49	12.70		2.33	14.19	.79
FAGUG67	11481	13.5 15.5	2.0	95	4A43	3.34	.06	2.09	3.20	45.0	1.23	1.91	13.80		5.29	15.71	.61
FAGUG67	11482	15.5 18.2	2.7	100	4A43	3.56	.11	3.60	8.40	56.0	1.71	1.86	15.50		12.00	17.36	.70
FAGUG67	11483	18.2 20.2	2.0	100	4E4	4.46	.14	9.70	14.50	140.0	2.74	2.25	24.80		24.20	27.05	.60
FAGUG67	11484	20.2 22.4	2.2	100	4E4	4.86	.23	11.10	16.10	134.0	4.18	1.91	25.20		27.20	27.11	.59
FAGUG67	11485	22.4 24.4	2.0	100	4G4	4.63	.08	3.60	8.20	75.0	1.03	.57	15.00		11.80	15.57	.69
FAGUG67	11486	24.4 26.4	2.0	95	4G4	4.63	.06	5.70	13.40	112.0	.96	.62	13.80		19.10	14.42	.70
FAGUG67	11487	26.4 27.5	1.1	100	4E4	4.17	.12	5.90	13.20	95.0	1.44	2.07	20.30		19.10	22.37	.69
FAGUG67	11488	27.5 29.5	2.0	90	4E4	4.57	.12	3.20	19.50	45.0	1.17	1.59	27.60		22.70	29.19	.86
FAGUG67	11489	29.5 31.5	2.0	90	4E4	4.56	.10	5.80	24.00	83.0	1.10	2.23	23.20		29.80	25.43	.81
FAGUG67	11490	31.5 33.5	2.0	100	4E4	4.86	.09	5.70	22.00	85.0	.69	2.29	23.50		27.70	25.79	.79
FAGUG67	11491	33.5 35.4	1.9	100	4EA4	4.35	.21	5.30	16.40	140.0	.48	2.69	22.00		21.70	24.69	.76
FAGAG67	11492	139.3 140.4	1.1	100	4E41	3.84	.18	7.90	12.20	119.0	.48	4.63	12.00		20.10	16.63	.61
FAGAG67	11493	140.4 141.6	1.2	92	4E4	4.19	.11	10.60	18.90	178.0	1.17	2.83	16.50		29.50	19.33	.64
FAGAG67	11494	141.6 143.7	2.1	100	4A34	3.37	.07	3.00	5.70	50.0	.96	1.48	13.20		8.70	14.68	.66
FAGAG67	11495	143.7 144.1	.4	100	4D0	3.02	.06	2.60	6.90	45.0	.41	2.35	4.10		9.50	6.45	.73

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAC	PB+ZN	PC+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGA067	11496	145.5	147.3	1.8	100	4L13	3.00	.06	1.08	1.10	15.0	.41	1.52	4.17		2.18	5.69	.50
FAGA067	11497	147.3	149.1	1.8	100	4L13	3.04	.04	1.62	1.85	21.0	.62	1.45	4.88		3.47	6.33	.53
FAGA067	11498	149.1	150.9	1.8	94	4L13	2.98	.04	1.17	2.30	17.0	1.58	1.58	3.60		3.47	5.18	.66
FAGA067	11499	150.9	151.8	.9	78	4L14	2.94	.02	1.72	3.60	31.0	.27	1.78	1.88		5.32	3.66	.68
FAGA067	11500	151.8	152.3	.5	100	5C@	3.26	.02	1.10	4.20	21.0	.21	7.60	5.05		5.30	12.65	.79
FAGA067	11501	152.3	153.3	1.0	40	4DC	3.17	.05	3.30	4.70	52.0	.62	1.90	7.50		8.00	9.40	.59
FAGA067	11502	153.3	155.3	2.0	20	4L134	3.10	.03	.82	1.55	16.0	.34	2.81	6.10		2.37	8.91	.65
FAGA067	11503	161.9	162.5	.6	83	400		.03	1.73	4.30	32.0					6.03		.71
FAGA067	11504	162.5	163.6	1.1	64	4L0		.02	.59	.90	10.0					1.49		.60
FAGA067	11505	166.6	167.6	1.0	100	4A14	2.91	.03	2.02	3.60	35.0	.41	2.65	2.33		5.62	4.98	.64
FAGA067	11506	167.6	168.4	.8	88	4L14	3.00	.09	1.95	3.50	36.0	.55	1.80	5.70		5.45	7.50	.64
FAGA067	11507	173.6	175.1	1.5	100	4L14	3.06	.04	2.17	3.10	34.0	.55	1.04	4.54		5.27	5.58	.59
FAGA067	11508	175.1	177.7	2.6	92	4A1	3.04	.04	1.37	2.30	26.0	.62	1.71	3.98		3.67	5.69	.63
FAGA067	11509	177.7	180.3	2.6	96	4A1	3.02	.06	1.66	3.00	31.0	.69	1.04	2.83		4.66	3.87	.64
FAGA067	11510	180.3	182.8	2.5	96	4A1	2.98	.04	1.50	2.70	25.0	.62	1.38	2.50		4.20	3.88	.64
FAGA067	11511	184.9	186.5	1.6	100	4A10	3.20	.02	1.76	2.90	39.0	.34	1.11	9.80		4.66	10.91	.62
FAGA067	11512	189.0	190.7	1.7	100	4A1	2.95	.02	.71	2.40	15.0	.75	.97	1.16		3.11	2.13	.77
FAGA067	11513	190.7	192.4	1.7	100	4A1	2.89	.04	.52	1.62	13.0	.41	1.03	.85		2.14	1.88	.76
FAGA067	11514	192.4	194.2	1.8	89	4A14	3.02	.07	2.30	5.60	47.0	.48	1.45	1.81		7.90	3.26	.71
FAGA067	11515	196.0	197.9	1.9	89	4A14	3.38	.01	1.33	4.50	41.0	.69	1.11	12.10		5.83	13.21	.77
FAGA067	11516	197.9	199.8	1.9	100	4A14	3.25	.02	1.69	4.10	55.0	.69	1.17	9.70		5.79	10.87	.71
FAGA067	11517	199.8	201.7	1.9	95	4A14	3.22	.02	2.30	5.70	62.0	.69	1.11	7.30		8.00	8.41	.71
FAGA067	11518	201.7	203.0	1.3	77	4A14	3.28	.03	4.40	11.00	98.0	.69	1.38	6.10		15.40	7.48	.71
FAGA067	11519	203.0	204.4	1.4	100	4A14	3.46	.03	3.50	7.30	67.0	.75	1.52	10.00		10.80	11.52	.68
FAGA067	11520	205.7	207.0	1.3	92	4A34	3.56	.10	2.70	4.40	64.0	2.06	1.71	14.40		7.10	16.11	.62
FAGA067	11521	207.0	208.3	1.3	77	4A34	3.60	.07	5.20	7.60	84.0	1.51	1.45	12.40		12.80	13.85	.59
FAGA067	11522	208.3	210.0	1.7	94	4G4	4.01	.08	3.60	7.80	67.0	1.37	1.26	16.60		11.40	17.86	.68
FAGA067	11523	210.0	210.3	.3	100	4C0	3.36	.01	.53	1.72	16.0	.27	.76	11.90		2.25	12.66	.76
FAGA067	11524	210.6	211.7	1.1	100	4A0	3.05	.01	1.16	1.84	22.0	.27	.83	5.20		3.00	6.03	.61
FAGA067	11525	211.7	212.8	1.1	91	4A4	3.04	.01	2.30	4.30	44.0	.41	.90	3.64		6.60	4.54	.65
FAGA067	11526	212.8	213.4	.6	50	4K1	4.08	.01	.72	2.50	21.0	.48	1.04	22.50		3.22	23.54	.78
FAGA067	11527	213.4	214.0	.6	100	4A0	3.04	.01	1.45	2.90	28.0	.34	.90	4.79		4.35	5.69	.67
FAGA067	11528	229.2	230.6	1.4	93	4E14		.02	5.40	7.50	111.0					12.90		.58
FAGA067	11529	237.8	239.3	1.5	100	4D4	3.73	.14	7.30	12.20	142.0	.89	2.51	10.10		19.50	12.61	.63
FAGA067	11530	239.3	240.1	.8	100	4A34	3.53	.08	4.40	4.40	69.0	1.51	2.46	11.90		8.80	14.36	.50
FAGA067	11531	243.5	244.1	.6	83	4A14	3.50	.07	3.60	4.30	53.0	1.85	1.38	12.60		7.90	13.98	.54
FAGA067	11532	244.8	246.3	1.5	100	4A1	2.88	.03	.59	1.04	10.0	.34	1.87	3.48		1.63	5.35	.64
FAGA067	11533	246.3	247.8	1.5	73	4A1	2.95	.06	.74	1.60	14.0	.69	1.64	5.04		2.34	6.68	.68
FAGA067	11534	277.7	279.2	1.5	73	4L3		.02	.47	.67	6.0					1.14		.59
FAGA067	11535	279.2	280.8	1.6	31	4L3		.01	2.20	1.73	18.0					3.93		.44
FAGA067	11536	283.2	284.1	.9	100	4L0	3.12	.03	.77	.42	8.0	2.88	1.38	4.95		1.19	6.33	.35
FAGA067	11537	285.0	287.1	2.1	76	4E64	4.70	.20	5.20	7.80	95.0	1.65	1.11	31.50		13.00	32.61	.60
FAGA067	11538	287.1	289.0	1.9	89	4A3	3.27	.07	1.89	2.50	31.0	.82	1.49	13.70		4.39	15.19	.57
FAGA067	11539	307.5	310.3	2.8	32	4A1		.06	.57	.77	12.0					1.34		.58
FAGA067	11540	310.3	311.5	1.2	8	4A1		.11	.48	1.38	13.0					1.86		.74
FAGA067	11541	311.5	313.3	1.8	39	4A1		.01	.14	.47	3.0					.61		.77
FAGA067	11542	319.8	320.8	1.0	90	4L0		.05	.29	.77	5.0					1.06		.73
FAGA067	11543	320.8	322.8	2.0	60	4C38	3.60	.20	1.61	1.95	24.0	1.10	11.30	13.80		3.56	25.10	.55
FAGA067	11544	322.8	324.8	2.0	90	4C38	3.51	.26	.81	1.26	14.0	.62	10.10	13.10		2.07	23.20	.61
FAGA067	11545	339.8	341.3	1.5	80	4A0	3.15	.05	1.51	3.10	23.0	.96	2.03	5.99		4.61	8.02	.67

DDH	SAMPLE	---DEPTHS---	INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	SAO	PB+ZN	PO+PY	ZN
		FROM	TO	M	%	UNIT	%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGA067	11546	341.3	342.3	1.0	60	4EC#	3.51	.13	3.10	4.70	61.0	.27	1.65	.79	7.80	2.44	.60
FAGA067	11547	342.3	343.7	1.4	86	4A0	3.05	.03	1.10	2.09	17.0	.41	1.82	3.58	3.19	5.40	.66
FAGA067	11548	343.7	345.0	1.3	69	4A0	3.47	.07	1.13	1.92	23.0	.41	3.52	9.70	3.05	13.22	.63
FAGA067	11549	346.8	347.9	1.1	73	4G0	3.97	.06	3.10	4.90	55.0	.89	2.01	7.30	8.00	9.31	.61
FAGA067	11550	349.5	350.9	1.4	71	4G4#	4.42	.09	5.20	7.90	91.0	1.03	2.37	9.90	13.10	12.27	.60
FAGA067	11551	350.9	351.3	.4	100	4K4	4.05	.09	4.60	7.40	66.0	.69	2.25	12.40	12.00	14.65	.62
FAGA067	11552	351.3	353.3	2.0	90	4E84	4.78	.21	3.60	2.40	48.0	1.44	5.10	23.20	6.00	28.30	.40
FAGA067	11553	353.3	354.6	1.3	100	4C3#	3.67	.21	4.80	.98	92.0	1.10	2.14	20.70	5.78	22.84	.17
FAGA067	11554	354.6	355.0	.4	100	4E0	4.07	.23	.70	.58	17.0	1.51	3.45	21.80	1.28	25.25	.45
FAGA067	11555	373.7	375.1	1.4	100	4A0		.10	.20	.16	7.0				.36		.44
FAGA067	11556	375.1	375.9	.8	100	4C0		.20	.29	.28	13.0				.57		.49
FAGA067	11557	375.9	377.2	1.3	69	4A3		.20	.20	.28	8.0				.48		.58
FAGA214	11558	53.0	55.8	2.8	25	4A4*	3.23	.03	2.70	3.50	44.0	.34	4.16	6.00	6.20	10.16	.56
FAGA214	11559	67.7	68.3	.6	83	4AE	3.55	.02	3.90	6.30	69.0	.48	2.73	5.80	10.20	8.53	.62
FAGA214	11560	68.3	69.1	.8	87	5D*	3.20	.05	2.90	3.30	59.0	1.44	5.01	1.92	6.20	6.93	.53
FAGA214	11561	69.1	69.5	.4	100	4D4	3.23	.03	4.00	7.70	62.0	1.17	2.86	2.83	11.70	5.69	.66
FAGA214	11562	70.8	71.5	.7	100	4C0	3.56	.07	1.61	2.50	29.0	.89	2.73	15.40	4.11	18.13	.61
FAGA214	11563	71.8	72.2	.4	100	4CA	3.09	.09	1.56	1.90	23.0	.69	1.88	3.32	3.46	5.20	.55
FAGA214	11564	74.2	74.7	.5	100	4D4	3.41	.09	5.70	4.70	62.0	.62	1.82	7.80	10.40	9.62	.45
FAGA214	11565	75.9	76.2	.3	100	4E4	4.78	.08	11.10	20.20	200.0	1.30	3.81	15.30	31.30	19.11	.65
FAGA214	11566	76.2	76.6	.4	75	4A0	3.41	.01	.83	1.75	18.0	.48	1.22	9.50	2.58	10.72	.68
FAGA214	11567	76.6	77.0	.4	75	4E4	4.63	.02	7.30	14.40	135.0	1.30	1.61	27.30	21.70	28.91	.66
FAGA214	11568	77.0	78.0	1.0	100	4A4	3.51	.02	3.00	6.40	56.0	.55	1.44	9.90	9.40	11.34	.68
FAGA214	11569	78.0	79.5	1.5	100	4E4*	3.89	.02	5.90	13.70	115.0	.82	2.13	13.00	19.60	15.13	.70
FAGA214	11570	79.5	80.9	1.4	100	4E4*	3.99	.08	8.50	15.70	153.0	1.03	2.49	13.20	24.20	15.69	.65
FAGA214	11571	80.9	81.4	.5	100	4A0	2.99	.02	.22	.38	4.0	.14	1.70	2.77	.60	4.47	.63
FAGA214	11572	81.4	82.5	1.1	100	4E4	4.05	.04	5.50	14.30	111.0	.69	6.50	15.50	19.80	22.00	.72
FAGA214	11573	82.5	84.5	2.0	100	4D4	3.18	.02	4.30	11.50	82.0	.21	3.45	2.25	15.80	5.70	.73
FAGA214	11574	84.5	86.5	2.0	100	4D4	3.17	.03	3.00	9.40	58.0	.27	3.10	2.69	12.40	5.79	.76
FAGA214	11575	86.5	88.0	1.5	100	4D4	3.31	.02	5.20	11.60	104.0	.34	2.13	2.24	16.80	4.37	.69
FAGA214	11576	93.0	93.4	.4	100	4A41	3.38	.02	2.90	7.70	55.0	.34	2.07	7.70	10.60	9.77	.73
FAGA214	11577	93.4	94.1	.7	100	4A0	3.04	.01	.11	.30	3.0	.07	1.01	3.46	.41	4.47	.73
FAGA214	11578	94.1	94.7	.6	100	4E4	4.47	.01	1.65	6.70	22.0	.82	1.17	34.70	8.35	35.87	.80
FAGA214	11579	94.7	95.4	.7	100	4A14	3.20	.01	3.90	11.70	63.0	.27	1.82	1.31	15.60	3.13	.75
FAGA214	11580	95.4	96.8	1.4	100	4A0	2.96	.01	.08	.17	3.0	.07	2.01	1.28	.25	3.29	.68
FAGA214	11581	98.6	100.6	2.0	100	4A0	2.96	.01	.71	1.46	16.0	.07	2.07	1.22	2.17	3.29	.67
FAGA214	11582	100.6	102.1	1.5	60	4A0	2.98	.01	1.12	3.30	22.0	.14	1.08	1.08	4.42	2.16	.75
FAGA214	11583	180.8	182.8	2.0	100	5A19		.01	.03	.08	3.0				.11		.73
FAGA214	11584	182.8	184.8	2.0	100	5A19		.01	.05	.09	3.0				.14		.64
FAGA214	11585	184.8	186.8	2.0	90	5A19		.01	.05	.11	3.0				.16		.69
FAGA214	11586	186.8	188.9	2.1	81	5A19		.01	.02	.04	1.0				.06		.67
FAGU071	11587	.0	.9	.9	56	4C1	3.09	.05	.42	.42	10.0	.48	.93	9.80	.84	10.73	.50
FAGU071	11588	.9	1.3	.4	100	4L0	2.95	.01	.11	.13	5.0	.07	4.06	2.92	.24	6.98	.54
FAGU071	11589	1.3	3.1	1.8	100	4A1	3.19	.08	1.91	1.13	32.0	1.23	.49	11.00	3.04	11.49	.37
FAGU071	11590	3.1	4.9	1.8	94	4A14	3.15	.05	3.40	4.50	42.0	.82	.86	6.90	7.90	7.76	.57
FAGU071	11591	4.9	6.1	1.2	67	4A3	3.38	.02	1.15	2.70	23.0	.62	1.32	14.40	3.85	15.72	.70
FAGU071	11592	6.1	7.9	1.8	100	4A34	3.50	.06	2.11	4.90	44.0	1.78	1.05	16.90	7.01	17.95	.70
FAGU071	11593	7.9	9.8	1.9	74	4A34	3.39	.04	2.50	5.60	43.0	.82	1.05	14.20	8.10	15.25	.69
FAGU071	11594	9.8	11.2	1.4	93	4E4	4.60	.02	13.50	23.00	209.0	1.03	1.51	16.90	36.50	18.41	.63
FAGU071	11595	11.2	12.6	1.4	71	4E4	4.58	.14	9.80	19.60	166.0	1.10	2.44	23.30	29.40	25.74	.67

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAO	PB+ZN	PC+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGU071	11596	12.6	14.8	2.2	95	4A34	3.24	.07	2.20	4.50	37.0	.82	1.12	14.50		6.70	15.62	.67
FAGU071	11597	14.8	17.0	2.2	100	4A34	3.17	.03	3.30	7.60	56.0	.48	1.38	10.50		10.90	11.88	.70
FAGU071	11598	17.0	17.3	.3	100	4E4	3.80	.05	5.80	13.20	103.0	.62	1.12	20.00		19.00	21.12	.69
FAGU071	11599	17.3	19.3	2.0	90	4AE4	3.49	.05	2.80	5.80	53.0	.82	.64	15.80		8.60	16.44	.67
FAGU071	11600	19.3	21.3	2.0	90	4AE4	3.34	.06	5.40	15.10	97.0	.69	1.38	10.50		20.50	11.88	.74
FAGU071	11601	21.3	21.7	.4	100	4E4	3.89	.04	7.50	17.80	133.0	.62	1.64	17.70		25.30	19.34	.70
FAGU071	11602	21.7	22.8	1.1	64	4EA4	3.32	.06	5.40	9.70	83.0	.89	1.19	9.30		15.10	10.49	.64
FAGU071	11603	22.8	24.3	1.5	80	4EA4	3.50	.12	7.90	12.40	126.0	1.44	1.25	11.10		20.30	12.35	.61
FAGU071	11604	24.3	24.7	.4	75	4E84	4.30	.03	12.10	20.10	150.0	3.02	5.60	15.80		32.20	21.40	.62
FAGU071	11605	24.7	26.2	1.5	67	5A69	3.16	.03	1.86	3.70	35.0	.27	2.96	8.10		5.56	11.06	.67
FAGA010	11606	154.4	155.1	.7	86	4D4	3.27	.04	1.93	4.80	47.0	.14	5.90	8.00		6.73	13.90	.71
FAGA010	11607	158.3	160.5	2.2	59	4E4	4.19	.16	6.20	12.90	117.0	1.78	1.45	23.50		19.10	24.95	.68
FAGA010	11608	160.5	160.9	.4	75	4A13	4.13	.08	2.80	5.20	55.0	1.51	.87	29.80		8.00	30.67	.65
FAGAC10	11609	160.9	161.5	.6	100	4E0	4.50	.18	.67	.72	23.0	1.85	2.31	39.80		1.39	42.11	.52
FAGAC10	11610	161.5	163.0	1.5	87	4EA4	3.90	.17	2.06	3.50	53.0	1.65	2.37	27.30		5.56	29.67	.63
FAGAC10	11611	163.0	164.5	1.5	93	4EA4	3.93	.19	2.90	3.50	51.0	1.85	1.76	26.20		6.40	27.96	.55
FAGAC10	11612	164.5	166.0	1.5	100	4A4	3.41	.03	6.50	12.00	104.0	.75	2.31	7.60		18.50	9.91	.65
FAGAC10	11613	166.0	166.5	.5	100	4E4	4.28	.13	6.90	16.70	114.0	1.17	1.64	19.00		23.60	20.64	.71
FAGAC10	11614	166.5	168.3	1.8	100	4A41	3.21	.02	3.60	9.30	62.0	.48	1.70	5.40		12.90	7.10	.72
FAGAC10	11615	168.3	170.1	1.8	89	4A10	3.35	.16	1.08	2.70	26.0	.82	1.82	15.10		3.78	16.92	.71
FAGAC10	11616	170.1	171.9	1.8	83	4A41	3.44	.10	3.40	6.30	65.0	.96	1.94	9.90		9.70	11.84	.65
FAGAC10	11617	171.9	173.7	1.8	100	4E4	4.89	.20	8.30	14.70	140.0	1.71	1.51	25.90		23.00	27.41	.64
FAGAC10	11618	173.7	175.5	1.8	100	4E4	4.45	.12	8.50	15.60	130.0	1.65	2.27	24.50		24.10	26.77	.65
FAGAC10	11619	175.5	177.5	2.0	80	4A4	3.74	.10	4.50	9.60	67.0	1.23	2.31	14.30		14.10	16.61	.68
FAGAC10	11620	177.5	179.0	1.5	87	4A0	3.17	.03	1.41	3.20	29.0	.48	1.64	7.90		4.61	9.54	.69
FAGAC10	11621	179.0	180.6	1.6	100	4A4	3.01	.01	1.44	4.10	25.0	.62	1.31	1.44		5.54	2.75	.74
FAGAC10	11622	180.6	182.1	1.5	100	4A4	2.99	.02	2.40	5.00	31.0	.27	1.38	1.77		7.40	3.15	.68
FAGAC10	11623	182.1	183.6	1.5	100	4A4	3.03	.02	3.20	5.40	40.0	.41	1.45	2.80		8.60	4.25	.63
FAGAC10	11624	183.6	184.6	1.0	100	4A41	3.22	.08	4.80	6.10	56.0	.75	1.51	6.22		10.90	7.73	.56
FAGAC10	11625	184.6	185.2	.6	83	4A41	3.07	.04	2.80	5.50	30.0	.55	1.52	2.93		8.30	4.45	.66
FAGAC10	11626	185.2	186.8	1.6	94	4A14	3.25	.05	6.00	1.65	58.0	1.51	1.19	8.30		7.65	9.49	.22
FAGAC10	11627	186.8	188.3	1.5	100	4A14	3.32	.08	6.30	2.11	63.0	1.23	1.32	9.80		8.41	11.12	.25
FAGAC10	11628	188.3	189.9	1.6	100	4A13	3.10	.06	1.33	.60	22.0	1.30	1.09	9.60		1.93	10.69	.31
FAGAC10	11629	189.9	191.8	1.9	100	4A13	3.09	.06	.66	.39	16.0	.82	1.33	8.30		1.05	9.63	.37
FAGAC10	11630	191.8	193.8	2.0	90	4A13	3.04	.08	.33	.50	7.0	.69	1.47	9.10		.83	10.57	.60
FAGAC10	11631	193.8	194.8	1.0	90	4A1	2.99	.10	.14	.14	6.0	.48	1.43	9.10		.28	10.53	.50
FAGAC10	11632	194.8	196.7	1.9	89	4A1	3.08	.11	1.01	.82	16.0	.75	1.60	10.30		1.83	11.90	.45
FAGAC10	11633	196.7	198.6	1.9	100	4A1	2.92	.06	.43	.25	9.0	.55	1.61	5.50		.68	7.11	.37
FAGAC10	11634	198.6	200.6	2.0	75	4A1	2.95	.06	.27	.47	7.0	.55	1.51	6.00		.74	7.51	.63
FAGAC10	11635	200.6	202.1	1.5	67	4L12	2.97	.02	.11	.54	6.0	.27	5.40	3.78		.65	9.18	.83
FAGAC10	11636	202.1	203.7	1.6	100	4A1	2.98	.05	.50	1.27	13.0	.62	1.76	7.50		1.77	9.26	.72
FAGAC10	11637	203.7	204.6	.9	100	4A1	3.00	.05	.29	.90	8.0	.75	1.42	7.10		1.19	8.52	.76
FAGAC10	11638	204.6	206.4	1.8	94	4A1	3.08	.05	.46	.95	10.0	.62	1.25	5.50		1.41	6.75	.67
FAGAC10	11639	206.4	207.9	1.5	100	4A10	3.18	.07	.86	1.50	18.0	.89	1.47	9.50		2.36	10.97	.64
FAGAC10	11640	207.9	209.3	1.4	86	4A14	3.38		1.87	3.20	37.0	1.30	1.68	9.90		5.07	11.58	.63
FAGAC10	11641	209.3	210.2	.9	100	4A21	3.66		.25	1.04	19.0	.82	2.31	21.90		1.29	24.21	.81
FAGAC10	11642	210.2	211.6	1.4	100	4A41	3.84		2.60	4.60	43.0	.89	1.74	7.90		7.20	9.64	.64
FAGAC10	11643	211.6	213.0	1.4	86	4A10	3.82		1.64	2.50	36.0	.96	1.10	8.60		4.14	9.70	.60
FAGAC10	11644	213.0	213.7	.7	71	4A13	3.33		.33	.84	15.0	.62	1.47	11.20		1.17	12.67	.72
FAGAC10	11645	213.7	215.4	1.7	100	4L21	3.02		.30	.70	13.0	.34	.61	5.70		1.00	6.31	.70

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAO	PB+ZN	PO+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGA010	11646	215.4	217.2	1.8	61	4L21	3.02		.36	.53	14.0	.41	.88	6.50		.89	7.38	.60
FAGA010	11647	217.2	218.8	1.6	81	4A14	3.18		1.86	3.60	37.0	.96	.99	9.30		5.46	10.29	.66
FAGA010	11648	218.8	220.4	1.6	62	4A10	3.52		1.68	3.20	36.0	.69	2.24	10.50		4.88	12.74	.66
FAGA010	11649	220.4	222.0	1.6	100	4E0	3.92		.14	1.07	19.0	.82	3.10	27.70		1.21	30.80	.88
FAGA010	11650	222.0	222.5	.5	80	4A134	3.96		2.70	3.10	59.0	1.23	2.50	26.70		5.80	29.20	.53
FAGA010	11651	222.5	223.2	.7	57	4D4	4.24		8.70	12.60	137.0	1.37	3.17	21.10		21.30	24.27	.59
FAGA010	11652	223.2	224.6	1.4	93	4G4	4.49		5.60	11.30	93.0	1.44	1.68	20.30		16.90	21.98	.67
FAGA010	11653	224.6	226.1	1.5	87	4E4#	4.43		4.70	7.90	100.0	1.44	1.74	29.00		12.60	30.74	.63
FAGA010	11654	226.1	227.8	1.7	100	4E4#	4.51		5.60	8.60	115.0	1.73	1.33	28.40		14.20	29.73	.61
FAGA010	11655	227.8	229.6	1.8	89	4E4#	4.50		2.70	5.40	59.0	1.03	1.47	33.00		8.10	34.47	.67
FAGA010	11656	229.6	230.1	.5	100	4G4	4.73		4.80	8.00	91.0	1.44	.97	22.60		12.80	23.57	.63
FAGA010	11657	233.6	234.2	.6	83	4D0#	3.89		3.80	5.80	138.0	1.23	2.37	20.20		9.60	22.57	.60
FAGA010	11658	234.2	234.8	.6	67	4C0	3.66		1.11	2.90	37.0	2.47	2.06	18.90		4.01	20.96	.72
FAGA010	11659	234.8	235.2	.4	75	4G4#	4.17		5.70	12.10	180.0	1.17	1.55	8.40		17.80	9.95	.68
FAGA010	11660	235.2	235.5	.3	100	4A4	3.90		3.60	7.10	76.0	.21	4.34	13.80		10.70	18.14	.66
FAGA010	11661	235.5	236.4	.9	56	4G4	4.49		3.40	10.80	49.0	.21	1.68	17.00		14.20	18.68	.76
FAGA010	11662	237.5	238.0	.5	100	4G0	4.28	.04	2.80	5.50	50.0	.34	1.74	18.80		8.30	20.54	.66
FAGA010	11663	239.3	240.0	.7	86	4G4	4.30	.12	4.20	15.50	91.0	.89	1.33	17.00		19.70	18.33	.79
FAGA010	11664	244.5	245.0	.5	100	4G4	4.42	.12	5.30	9.60	96.0	.89	1.47	14.30		14.90	15.77	.64
FAGA010	11665	245.5	246.8	1.3	54	4G4	4.84	.22	6.70	9.70	109.0	1.23	2.37	21.40		16.40	23.77	.59
FAGA010	11666	246.8	247.6	.8	100	4G4	4.61	.12	4.10	7.60	77.0	1.17	.55	20.80		11.70	21.35	.65
FAGA010	11667	247.6	247.9	.3	67	4E0	4.67	.08	3.80	5.80	59.0	.75	2.06	30.00		9.60	32.06	.60
FAGA010	11668	247.9	248.4	.5	100	4C0	3.68	.10	.69	.74	18.0	.27	6.30	16.30		1.43	22.60	.52
FAGA072	11669	156.7	157.4	.7	100	4AE	3.60	.04	5.80	12.90	89.0	.96	1.55	9.70		18.70	11.25	.69
FAGA072	11670	157.4	159.5	2.1	100	4A3	3.43	.07	1.58	3.00	34.0	.96	1.33	15.20		4.58	16.53	.66
FAGA072	11671	159.5	160.5	1.0	90	4A3	3.44	.05	.88	1.43	26.0	.82	1.18	19.20		2.31	20.38	.62
FAGA072	11672	160.5	160.9	.4	100	4A3	3.56	.02	1.33	3.00	32.0	.55	1.92	12.80		4.33	14.72	.69
FAGA072	11673	162.5	162.9	.4	75	4C0	3.24	.07	2.60	.35	35.0	.41	3.06	7.10		2.95	10.16	.12
FAGA072	11674	163.5	163.8	.3	67	4A13	3.14	.05	1.44	.40	26.0	.75	4.28	8.70		1.84	12.98	.22
FAGA072	11675	163.8	165.1	1.3	100	4L0	3.81	.03	.37	.80	9.0	.21	1.59	2.53		1.17	4.12	.68
FAGA072	11676	165.1	166.2	1.1	82	4L0	3.12	.05	.50	1.18	14.0	.27	1.59	5.30		1.68	6.89	.70
FAGA072	11677	166.2	168.2	2.0	90	4L14	3.07	.06	1.11	1.89	21.0	.41	1.52	6.30		3.00	7.82	.63
FAGA072	11678	168.2	169.8	1.6	81	4L1	2.94	.03	.60	1.58	14.0	.41	1.25	4.44		2.18	5.69	.73
FAGA072	11679	169.8	171.1	1.3	92	4L14	3.05	.05	.97	2.60	20.0	.48	1.45	4.70		3.57	6.15	.73
FAGA072	11680	171.1	172.5	1.4	86	4L14	3.06	.05	1.18	2.20	20.0	.69	1.45	6.20		3.38	7.65	.65
FAGA072	11681	172.5	173.6	1.1	100	4A1	2.89	.04	1.77	1.66	26.0	.41	1.25	1.89		3.43	3.14	.48
FAGA072	11682	173.6	174.7	1.1	100	4L14	2.95	.03	1.74	4.00	36.0	.27	1.52	1.42		5.74	2.94	.70
FAGA072	11683	175.8	177.0	1.2	83	4L14	2.94	.03	1.00	2.50	20.0	.21	3.40	1.80		3.50	5.20	.71
FAGA072	11684	177.0	177.4	.4	100	4A14	3.02	.08	2.90	4.00	44.0	.89	1.52	6.00		6.90	7.52	.58
FAGA072	11685	177.4	178.7	1.3	100	4L1	2.96	.06	.64	1.30	12.0	.34	2.17	4.31		1.94	6.48	.67
FAGA072	11686	178.7	180.2	1.5	100	4A1	2.99	.06	.41	.87	10.0	.41	1.45	7.10		1.28	8.55	.68
FAGA072	11687	180.2	181.7	1.5	87	4A1	3.00	.05	.45	1.09	10.0	.41	1.52	6.70		1.54	8.22	.71
FAGA072	11688	181.7	183.1	1.4	100	4A34	3.24	.11	2.70	3.40	45.0	1.03	1.35	12.20		6.10	13.55	.56
FAGA072	11689	184.0	185.3	1.3	85	4A14	3.04	.06	1.19	2.60	27.0	.62	2.75	5.20		3.79	7.95	.69
FAGA072	11690	194.6	195.1	.5	100	4A4		.04	2.70	5.70	54.0					8.40		.68
FAGA010	11700	156.4	158.3	1.9	95	4A0	3.12	.04	1.39	2.40	30.0	1.03	2.11	8.50		3.79	10.61	.63
FAGA084	11701	148.7	149.2	.5	100	4E8		.23	1.20	.86	27.0					2.06		.42
FAGA084	11702	151.2	152.4	1.2	92	4E9	3.37	.19	.98	1.02	25.0	.48	9.90	11.50		2.00	21.40	.51
FAGA084	11703	152.4	153.2	.8	87	4E1#	3.48	.29	1.53	1.68	40.0	.34	6.80	15.30		3.21	22.10	.52

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAC	PB+ZN	PO+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGA084	11704	153.2	153.5	.3	67	4E4	3.65	.05	6.90	8.20	72.0	.27	3.56	14.60		15.10	18.16	.54
FAGA084	11705	200.4	201.1	.7	71	4E1		.08	.35	.40	13.0					.75		.53
FAGA084	11706	215.5	215.6	.1	100	4A0		.04	.43	2.70	14.0					3.13		.86
FAGA084	11709	219.2	220.5	1.3	100	4A0		.02	.39	.73	9.0					1.12		.65
FAGA084	11712	255.8	256.2	.4	75	4C75		.15	1.67	2.70	37.0					4.37		.62
FAGA084	11713	256.2	257.9	1.7	100	4A13		.13	.14	.22	7.0					.36		.61
FAGA084	11714	257.9	258.3	.4	100	4E1		.11	1.12	1.25	27.0					2.37		.53
FAGA084	11715	258.3	258.8	.5	100	4G0		.14	1.38	1.37	26.0					2.75		.50
FAGA084	11716	258.8	259.1	.3	100	4E17		.10	.81	.65	24.0					1.46		.45
FAGA084	11717	277.8	277.9	.1	100	4E17	3.78	.08	1.79	2.20	43.0	.07	13.70	18.40		3.99	32.10	.55
FAGA084	11718	277.9	278.6	.7	100	4L0	3.36	.09	1.11	1.05	24.0	.21	6.80	13.20		2.16	20.00	.49
FAGA084	11719	278.6	279.8	1.2	100	4K81	3.78	.10	1.21	1.26	27.0	.55	5.80	23.80		2.47	29.60	.51
FAGA084	11720	279.8	280.1	.3	100	4K1		.10	.27	.12	17.0					.39		.31
FAGA084	11721	280.1	280.6	.5	80	4A1		.09	.20	.10	7.0					.30		.33
FAGA084	11722	280.6	281.0	.4	100	4K1		.10	.51	.36	18.0					.87		.41
FAGA084	11723	282.7	283.6	.9	89	4E1		.01	.07	.31	6.0					.38		.82
FAGA084	11724	283.6	284.4	.8	75	4A0		.05	.08	.47	4.0					.55		.85
FAGA084	11725	284.4	286.7	2.3	100	4K1		.12	.22	.19	13.0					.41		.46
FAGA084	11726	286.7	287.7	1.0	90	4A1		.06	.66	1.24	15.0					1.90		.65
FAGA084	11727	314.1	316.0	1.9	95	4A31		.16	.07	.27	7.0					.34		.79
FAGA084	11728	318.5	318.8	.3	67	4G8	3.95	.13	3.20	2.70	42.0	.89	7.70	20.70		5.90	28.40	.40
FAGA084	11729	318.8	319.1	.3	67	4L12	3.62	.16	2.70	1.59	40.0	.27	13.10	12.00		4.29	20.10	.57
FAGA084	11730	319.1	319.3	.2	100	4C0	3.40	.13	2.70	1.86	39.0	.27	10.30	9.90		4.50	20.20	.47
FAGU068	11734	.0	2.0	2.0	100	4A0	3.07	.06	.46	.56	14.0	.82	.82	10.60		1.02	11.42	.55
FAGU068	11735	2.0	4.0	2.0	100	4A0	3.14	.08	1.51	.89	26.0	1.30	.72	12.60		2.40	13.52	.57
FAGU068	11736	4.0	6.0	2.0	100	4A0	3.02	.05	2.50	1.40	28.0	1.51	.78	7.88		3.90	8.66	.30
FAGU068	11737	6.0	7.3	1.3	92	4A4	2.88	.01	2.80	3.70	28.0	.62	1.07	24.60		6.50	25.67	.57
FAGU068	11738	7.3	9.3	2.0	100	4A4	2.93	.03	1.96	4.70	29.0	1.17	1.50	3.55		6.66	5.05	.71
FAGU068	11739	9.3	11.0	1.7	100	4A4	3.39	.06	3.70	7.50	51.0	1.44	1.11	13.30		11.20	14.41	.67
FAGU068	11740	11.0	13.0	2.0	100	4E4	4.50	.13	8.90	17.30	131.0	1.85	2.25	23.10		26.20	25.35	.66
FAGU068	11741	13.0	15.0	2.0	100	4E4	4.76	.26	9.20	15.50	159.0	3.84	1.39	27.00		24.70	28.39	.63
FAGU068	11742	15.0	17.0	2.0	90	4E4	4.76	.18	8.50	16.30	149.0	1.03	2.48	25.10		24.80	27.58	.66
FAGU068	11743	17.0	18.9	1.9	100	4E4	4.57	.06	4.50	11.50	91.0	1.10	1.73	27.30		16.00	29.03	.72
FAGU068	11744	18.9	21.1	2.2	100	4E54	3.93	.09	4.50	7.10	78.0	1.37	1.52	23.10		11.60	24.62	.61
FAGU068	11745	21.1	22.2	1.1	100	4A42	3.49	.03	3.60	4.60	68.0	1.23	2.10	15.50		8.20	17.60	.56
FAGU070	11746	.0	1.8	1.8	39	4A0	3.00	.03	.55	1.52	15.0	.55	3.67	6.74		2.67	10.41	.73
FAGU070	11747	1.8	3.8	2.0	70	4A0	3.07	.06	2.40	1.03	32.0	1.03	.79	9.72		3.43	10.51	.30
FAGU070	11748	3.8	6.6	2.8	89	4A24	3.18	.03	2.40	3.70	38.0	1.10	1.28	11.20		6.10	12.48	.61
FAGU070	11749	6.6	8.7	2.1	95	4A42	3.64	.08	8.00	11.70	120.0	1.99	1.52	13.90		19.70	15.42	.59
FAGU070	11750	8.7	10.8	2.1	100	4A42	3.90	.06	8.00	13.60	124.0	1.99	1.81	17.20		21.60	19.01	.63
FAGU070	11751	10.8	12.8	2.0	80	4E4	4.54	.17	9.40	19.60	136.0	2.19	1.87	21.90		29.00	23.77	.68
FAGU070	11752	12.8	14.8	2.0	80	4E4	4.64	.21	10.00	17.60	131.0	2.19	1.03	25.00		27.60	26.03	.64
FAGU070	11753	14.8	16.7	1.9	89	4E4	4.47	.10	7.90	15.60	138.0	.82	1.31	25.00		23.50	26.31	.66
FAGU070	11754	16.7	19.3	2.6	73	5D4\$	2.96	.01	.30	1.72	9.0	1.10	6.36	3.62		2.02	9.98	.85
FAGU070	11755	19.3	20.8	1.5	73	4A42	3.38	.11	3.00	6.10	45.0	1.44	1.08	13.30		9.10	14.38	.67
FAGU070	11756	20.8	22.2	1.4	100	4A42	3.35	.06	4.10	7.30	66.0	1.58	1.66	12.10		11.40	13.76	.64
FAGU070	11757	22.2	24.0	1.8	83	4E4	3.79	.11	6.90	12.70	120.0	1.44	1.57	14.80		19.60	16.37	.65
FAGU070	11758	24.0	25.2	1.2	42	4E4	4.02	.14	6.70	17.20	125.0	1.30	1.87	17.10		23.90	18.97	.72
FAGU069	11759	.0	1.5	1.5	73	4AL	3.01	.08	.50	.60	11.0	.75	2.66	7.52		1.10	10.18	.55
FAGU069	11760	1.5	3.3	1.8	67	4A0	3.01	.07	1.70	1.35	21.0	.89	1.23	7.87		3.05	9.10	.44

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAC	PB+ZN	PO+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGU069	11761	3.3	4.7	1.4	86	4A4	3.10	.05	2.60	4.60	40.0	.75	1.38	7.33		7.20	8.71	.64
FAGU069	11762	4.7	6.0	1.3	92	4A43	3.37	.04	2.00	4.20	41.0	1.03	1.33	15.00		6.20	16.33	.68
FAGU069	11763	6.0	8.0	2.0	80	4A43	3.78	.15	4.00	7.70	70.0	2.06	1.55	20.10		11.70	21.65	.66
FAGU069	11764	8.0	10.0	2.0	100	4E4	4.47	.33	7.10	14.50	139.0	2.06	1.66	24.50		21.60	26.16	.67
FAGU069	11765	10.0	11.4	1.4	93	4E4	4.50	.26	6.80	14.00	130.0	2.13	1.03	27.10		20.80	28.13	.67
FAGU069	11766	11.4	13.4	2.0	100	4A4	3.14	.07	1.81	4.60	40.0	.69	1.37	10.30		6.41	11.67	.72
FAGU069	11767	13.4	14.4	1.0	90	4A0	3.29	.14	.52	.75	16.0	1.10	1.53	16.10		1.27	17.63	.59
FAGU069	11768	14.4	16.4	2.0	100	4A41	3.22	.05	4.00	9.20	65.0	.96	1.82	8.16		13.20	9.98	.70
FAGU069	11769	16.4	18.4	2.0	100	4A41	3.31	.01	5.60	12.60	99.0	.69	1.81	6.70		18.20	8.51	.69
FAGU069	11770	18.4	20.4	2.0	90	4A41	3.21	.02	4.60	11.90	80.0	.62	1.89	5.86		16.50	7.75	.72
FAGU069	11771	20.4	22.0	1.6	94	4A41	3.19	.02	5.10	11.40	90.0	.82	1.81	5.82		16.50	7.63	.69
FAGU069	11772	22.0	23.5	1.5	87	4A41	3.84	.10	7.00	11.00	124.0	1.78	1.94	18.20		18.00	20.14	.61
FAGU069	11773	23.5	25.0	1.5	73	4E4	4.46	.13	6.40	10.50	119.0	1.65	1.28	26.10		16.90	27.38	.62
FAGU069	11774	25.0	26.7	1.7	18	4E4	4.46	.19	7.10	14.40	156.0	1.71	.86	19.40		21.50	20.26	.67
FAGU069	11775	26.7	27.4	.7	86	4G4	4.42	.43	5.60	12.50	134.0	2.88	.86	18.90		18.10	19.76	.69
FAGA214	11776	291.1	293.7	2.6	100	4GE4	4.46	.25	9.60	12.40	150.0	2.61	1.56	20.00		22.00	21.56	.56
FAGA214	11777	293.7	295.9	2.2	100	4DC	2.98	.04	1.23	2.50	25.0	.55	3.22	4.11		3.73	7.33	.67
FAGA214	11778	295.9	297.3	1.4	100	4L14	2.88	.02	.60	.74	6.0	.48	2.06	1.84		1.34	3.90	.55
FAGA214	11779	321.2	325.5	4.3	37	4E4	3.48	.03	2.10	3.20	40.0	.69	1.99	15.80		5.30	17.79	.60
FAGA214	11780	325.5	327.2	1.7	100	4A4	3.31	.07	2.20	3.90	44.0	1.10	2.07	13.60		6.10	15.67	.64
FAGU148	11781	3.6	5.6	2.0	100	4L41	2.90	.02	1.75	1.46	33.0	.89	3.39	1.88		3.21	5.27	.45
FAGU148	11782	5.6	7.6	2.0	100	4L41	2.85	.03	1.72	2.40	27.0	.55	2.52	1.13		4.12	3.65	.58
FAGU148	11783	7.6	9.8	2.2	100	4L41	2.85	.03	2.30	4.10	35.0	1.23	1.49	1.00		6.40	2.49	.64
FAGU148	11784	10.5	12.8	2.3	96	4CA		.07	.48	.77	10.0					1.25		.62
FAGU148	11785	27.3	29.3	2.0	90	4A41	2.81	.11	3.20	4.80	62.0	1.23	1.80	3.29		8.00	5.09	.60
FAGU148	11786	29.3	31.3	2.0	100	4A41	2.92	.06	2.10	3.10	38.0	1.17	1.22	4.07		5.20	5.29	.60
FAGU148	11787	31.3	33.4	2.1	100	4A41	2.99	.11	1.81	4.10	30.0	1.37	1.55	5.43		5.91	6.98	.69
FAGU148	11788	38.1	40.1	2.0	100	4A14	3.47	.07	3.00	4.30	49.0	1.85	3.03	15.40		7.30	18.43	.59
FAGU148	11789	40.1	42.7	2.6	100	4A14	3.72	.11	3.20	4.20	47.0	1.85	1.38	20.20		7.40	21.58	.57
FAGU148	11790	42.7	43.8	1.1	100	4A14	3.31	.06	5.20	6.70	74.0	1.85	1.26	7.91		11.90	9.17	.56
FAGU148	11791	43.8	45.3	1.5	100	4A14	3.43	.08	5.50	7.60	84.0	1.37	1.52	10.90		13.10	12.42	.58
FAGU148	11792	45.3	46.8	1.5	80	4A14	3.31	.06	3.30	3.80	55.0	1.78	1.02	11.90		7.10	12.92	.54
FAGU148	11793	46.8	48.8	2.0	100	4A10	2.89	.02	1.47	3.20	26.0	.48	.95	2.44		4.67	3.39	.69
FAGU148	11794	50.4	51.3	.9	89	4A10	2.89	.02	1.44	3.40	25.0	.48	1.01	.16		4.84	1.17	.70
FAGU148	11795	51.3	53.3	2.0	80	4A30	3.04	.03	1.83	2.90	31.0	.89	.92	6.16		4.73	7.08	.61
FAGU148	11796	53.3	55.3	2.0	80	4A43	3.28	.04	2.60	3.60	55.0	1.10	1.17	11.40		6.20	12.57	.58
FAGU148	11797	55.3	57.3	2.0	100	4A43	3.14	.02	3.10	5.60	59.0	2.40	.88	8.29		8.70	9.17	.64
FAGU148	11798	57.3	59.3	2.0	80	4A43	3.24	.05	3.30	7.00	63.0	1.17	1.07	8.99		10.30	10.06	.68
FAGU148	11799	59.3	61.3	2.0	40	4A43	3.19	.03	2.80	5.30	57.0	1.10	1.01	9.15		8.10	10.16	.65
FAGU148	11800	61.3	62.9	1.6	100	4A43	3.35	.06	3.20	5.20	56.0	1.58	1.06	11.90		8.40	12.96	.62
FAGU148	11801	62.9	64.2	1.3	100	4A4	3.04	.03	1.95	3.30	33.0	.69	.91	6.47		5.25	7.38	.63
FAGU148	11802	64.2	65.2	1.0	100	4A14	2.88	.04	1.87	3.40	31.0	.48	.99	1.60		5.27	2.59	.65
FAGU072	11803	.0	2.0	2.0	80	4A0	3.13	.10	2.20	1.30	30.0	.89	1.21	11.10		3.50	12.31	.37
FAGU072	11804	2.0	4.0	2.0	80	4A0	3.19	.11	1.85	.68	29.0	1.30	1.23	12.40		2.53	13.63	.27
FAGU072	11805	4.0	6.0	2.0	90	4A0	3.16	.12	3.00	.80	45.0	.82	1.10	11.40		3.80	12.50	.21
FAGU072	11806	6.0	8.0	2.0	100	4A0	3.12	.12	1.00	.47	20.0	.82	1.36	11.60		1.47	12.96	.32
FAGU072	11807	8.0	10.0	2.0	95	4A0		.10	.90	.73	18.0					1.63		.45
FAGU072	11808	10.0	11.7	1.7	88	4A0		.10	.58	.91	10.0					1.49		.61
FAGU072	11809	11.7	13.6	1.9	84	4A0		.06	.33	.54	9.0					.87		.62
FAGU072	11810	13.6	15.8	2.2	91	4ACL		.08	.24	.36	7.0					.60		.60

DDH	SAMPLE	---DEPTHS---	INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAO	PB+ZN	PO+PY	ZN
		FROM TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGU072	11811	15.8 17.3	1.5	80	4A0		.12	.26	.55	7.0					.81		.68
FAGU072	11812	17.3 19.0	1.7	94	4A10	3.08	.11	.85	1.73	20.0	.75	1.54	9.92		2.63	11.46	.68
FAGU072	11813	19.0 20.5	1.5	80	4A0	3.11	.09	1.73	2.00	26.0	1.10	1.38	10.60		3.73	11.98	.54
FAGU072	11814	20.5 22.2	1.7	88	4A4	4.04	.28	2.60	3.50	53.0	1.37	1.65	28.80		6.10	30.45	.57
FAGU072	11815	22.2 24.3	2.1	95	4AE	3.78	.21	.65	1.28	29.0	.89	1.36	26.40		1.93	27.76	.66
FAGU072	11816	24.3 25.9	1.6	69	4A34	3.01	.08	2.20	3.20	37.0	1.10	1.58	5.90		5.40	7.48	.59
FAGU072	11817	25.9 27.9	2.0	95	4A4	3.93	.23	2.03	3.10	41.0	1.30	1.76	27.00		5.13	28.76	.60
FAGU072	11818	27.9 30.4	2.5	92	4AE	3.81	.08	1.57	2.60	46.0	.82	2.00	19.90		4.17	21.90	.62
FAGU072	11819	40.5 42.0	1.5	93	4EC	3.41	.02	1.38	1.06	26.0	.27	5.00	15.00		2.44	20.00	.43
FAGU072	11820	42.0 42.7	.7	71	400	3.96	.15	3.00	5.20	69.0	.82	1.79	21.50		8.20	23.29	.63
FAGU072	11821	63.4 65.2	1.8	89	4EA		.06	1.45	2.30	27.0					3.75		.61
FAGU072	11822	104.7 106.0	1.3	100	4E60	4.26	.13	3.10	3.40	43.0	.55	1.87	27.20		6.50	29.07	.52
FAGU072	11823	103.0 104.7	1.7	100	4A03	3.49	.14	1.68	2.50	27.0	.82	2.23	17.40		4.18	19.63	.60
FAGU072	11824	106.0 107.5	1.5	93	4EA	3.13	.09	.70	.98	14.0	.75	3.81	10.40		1.68	14.21	.58
FAGU072	11825	107.5 109.0	1.5	87	4A13	3.08	.16	1.34	1.68	23.0	.69	3.79	7.77		3.02	11.56	.56
FAGU072	11826	110.2 111.7	1.5	93	4ES	4.11	.26	2.90	2.90	45.0	1.71	2.61	35.40		5.80	38.01	.50
FAGU072	11827	109.0 110.2	1.2	92	4A13	2.84	.03	.50	1.15	9.0	.27	1.99	1.27		1.65	3.26	.70
FAGU072	11828	116.8 118.0	1.2	100	4AEL	3.27	.09	.92	1.39	16.0	1.99	3.60	13.00		2.31	16.60	.60
FAGU072	11829	114.2 116.8	2.6	46	4A0	3.02	.10	.76	1.71	13.0	.21	1.88	8.07		2.47	9.95	.69
FAGU072	11830	118.0 120.0	2.0	100	4A0	2.99	.06	.90	1.52	21.0	.48	1.66	7.10		2.42	8.76	.63
FAGU072	11831	122.0 123.6	1.6	100	4EAH	3.96	.07	1.48	1.72	36.0	1.37	10.54	24.10		3.20	34.64	.54
FAGU072	11832	120.0 122.0	2.0	60	4A0	2.91	.03	1.00	1.69	19.0	.55	2.14	4.15		2.69	6.29	.63
FAGU072	11833	124.6 126.6	2.0	100	4D45	3.51	.16	7.20	12.70	126.0	2.19	2.65	10.00		19.90	12.65	.64
FAGU072	11834	123.6 124.6	1.0	80	4A4	2.86	.05	2.50	.71	5.0	2.61	1.45	3.90		3.21	5.35	.22
FAGU072	11835	126.6 128.6	2.0	100	4D45	3.56	.03	9.00	19.60	159.0	2.81	2.12	7.62		28.60	9.74	.69
FAGU072	11836	128.6 131.0	2.4	100	4D4	3.54	.10	7.30	15.70	115.0	1.85	2.37	7.37		23.00	9.74	.68
FAGU072	11837	131.0 132.9	1.9	100	4A30	3.78	.03	1.45	3.10	38.0	1.85	.73	23.70		4.55	24.43	.68
FAGU072	11838	132.9 134.1	1.2	100	4EG	4.03	.04	2.30	5.50	54.0	.27	.73	27.00		7.80	27.73	.71
FAGU072	11839	134.1 135.6	1.5	87	4D45	3.59	.11	8.80	14.20	141.0	1.44	2.35	9.17		23.00	11.52	.62
FAGU072	11840	135.6 137.1	1.5	100	4D45	3.62	.04	10.00	14.50	156.0	1.71	2.29	8.10		24.50	10.39	.59
FAGU079	11841	.0 2.5	2.5	80	4A0	3.18	.08	1.30	.91	21.0	.82	.62	11.90		2.21	12.52	.41
FAGU079	11842	2.5 4.9	2.4	92	4A0	2.99	.06	.47	.24	11.0	1.65	.37	5.81		.71	6.18	.34
FAGU079	11843	4.9 6.4	1.5	93	4A4	3.05	.04	3.70	3.20	44.0	1.51	.66	5.21		6.90	5.87	.46
FAGU079	11844	6.4 7.8	1.4	100	4A4		.02	3.17	2.60	34.0					5.77		.45
FAGU079	11845	7.8 9.8	2.0	100	4A4	3.06	.02	2.70	2.40	31.0	2.19	.43	5.44		5.10	5.87	.47
FAGU079	11846	9.8 11.8	2.0	100	4A0	2.96	.03	3.10	1.05	31.0	2.74	.88	4.57		4.15	5.45	.25
FAGU079	11847	11.8 13.8	2.0	100	4A0	3.19	.04	2.40	.65	28.0	1.51	1.17	13.50		3.05	14.67	.21
FAGU079	11848	13.8 15.4	1.6	100	4A0	3.09	.06	.95	.42	27.0	.41	1.25	11.30		1.37	12.55	.31
FAGU079	11849	15.4 16.7	1.3	100	4A0	3.31	.10	.90	.52	19.0	1.71	1.45	13.30		1.42	14.75	.37
FAGU079	11850	16.7 18.2	1.5	100	4A4	3.13	.11	3.30	5.70	41.0	1.17	1.46	10.60		9.00	12.06	.63
FAGU079	11851	18.2 19.7	1.5	100	4A0	3.16	.09	2.60	1.37	33.0	1.30	.61	11.40		3.97	12.01	.35
FAGU079	11852	19.7 21.7	2.0	100	4A4	3.18	.14	3.80	5.30	51.0	1.99	1.45	10.80		9.10	12.25	.58
FAGU079	11853	21.7 23.0	1.3	100	4A0	3.01	.07	1.66	.45	25.0	1.30	.37	8.00		2.11	8.37	.21
FAGU079	11854	23.0 25.0	2.0	95	4A4	3.07	.08	3.90	4.30	50.0	1.03	1.05	5.45		8.20	6.50	.52
FAGU079	11855	25.0 27.0	2.0	100	4A4	3.22	.08	2.50	3.60	40.0	1.10	.94	11.60		6.10	12.54	.59
FAGU079	11856	27.0 29.1	2.1	100	4A4	2.92	.16	5.10	5.00	96.0	2.19	1.15	18.30		10.10	19.45	.50
FAGU079	11857	29.1 31.2	2.1	100	4A4	3.56	.14	3.70	4.30	70.0	1.92	1.04	18.00		8.00	19.04	.54
FAGU079	11858	31.2 33.2	2.0	85	4E4	4.29	.22	1.83	3.20	34.0	1.51	1.91	34.20		5.03	36.11	.64
FAGU079	11859	33.2 35.2	2.0	95	4E4	4.61	.31	3.80	5.00	64.0	1.65	1.93	35.70		8.80	37.63	.57
FAGU079	11860	35.2 36.5	1.3	62	4E4	4.67	.28	4.30	10.00	97.0	2.19	2.68	29.00		14.30	31.68	.70

DDH	SAMPLE	---DEPTHS---		INT M	REC %	ROCK UNIT	S.G.	CU %	PB %	ZN %	AG G/MT	AU G/MT	PO %	PY %	BAO %	PB+ZN %	PC+PY %	ZN RATIO
		FROM	TO															
FAGU079	11861	64.7	66.6	1.9	100	4H2	3.65	.08	4.50	7.70	65.0	.27	11.40	10.20		12.20	21.60	.63
FAGU079	11862	66.6	68.6	2.0	100	4EH	4.07	.23	6.30	11.10	100.0	.48	9.34	17.90		17.40	27.24	.64
FAGU079	11863	68.6	70.6	2.0	100	4E4	4.63	.25	8.80	12.50	145.0	.62	3.31	26.40		21.30	29.71	.59
FAGU079	11864	70.6	72.6	2.0	100	4E4	4.34	.15	5.40	8.00	106.0	.75	1.43	23.90		13.40	25.33	.60
FAGU079	11865	72.6	74.6	2.0	100	4E46	4.54	.26	4.90	8.10	117.0	1.85	.78	22.60		13.00	23.38	.62
FAGU079	11866	74.6	76.6	2.0	95	4E4	4.50	.21	4.60	6.70	113.0	1.85	.92	26.20		11.30	27.12	.59
FAGU079	11867	76.6	78.4	1.8	100	4EG4	4.43	.14	5.80	9.80	127.0	2.81	1.23	24.20		15.60	25.43	.63
FAGU079	11868	78.4	80.1	1.7	94	4D7	3.20	.08	1.98	3.20	39.0	.48	3.73	7.89		5.18	11.62	.62
FAGA161	11869	36.3	40.3	4.0	43	4A0		.03	1.23	2.80	26.0					4.03		.69
FAGA161	11870	48.7	50.4	1.7	100	4A0	3.08	.05	1.68	3.30	36.0	3.91	1.85	8.35		4.98	10.20	.66
FAGA161	11871	50.4	51.5	1.1	100	4D0	3.04	.02	2.80	5.90	53.0	2.74	3.28	5.10		8.70	8.38	.68
FAGA161	11872	55.2	57.3	2.1	76	4A0	3.01	.09	.90	1.93	23.0	1.10	4.03	5.06		2.83	9.09	.68
FAGA161	11873	57.3	61.1	3.8	50	4A0	2.95	.02	.30	.54	4.0	.62	3.19	2.97		.84	6.16	.64
FAGA161	11875	63.1	64.6	1.5	67	4A0	3.08	.05	1.13	2.20	22.0	1.85	1.51	6.87		3.33	8.38	.66
FAGA161	11876	64.6	67.8	3.2	75	4A0	3.16	.10	1.01	2.90	23.0	1.23	2.26	10.80		3.91	13.06	.74
FAGA161	11877	67.8	69.8	2.0	100	4A4	3.08	.07	1.59	3.90	34.0	.41	1.50	8.70		5.49	10.20	.71
FAGA161	11878	69.8	71.5	1.7	100	4A0	3.17	.04	1.97	2.80	37.0	.55	1.47	11.60		4.77	13.07	.59
FAGA161	11879	71.5	73.8	2.3	43	4A4	3.13	.04	1.88	4.30	40.0	.55	1.36	9.95		6.18	11.31	.70
FAGA161	11880	73.8	76.8	3.0	23	4A0	3.09	.05	1.22	1.39	24.0	.62	1.34	10.60		2.61	11.94	.53
FAGA161	11881	76.8	81.0	4.2	100	4A0	3.17	.04	2.70	1.49	41.0	.41	1.35	11.70		4.19	13.05	.36
FAGA161	11883	81.0	82.7	1.7	88	4A4	3.15	.07	1.96	4.30	46.0	.75	1.38	9.60		6.26	10.98	.69
FAGA161	11884	82.7	84.3	1.6	69	4A4	3.06	.06	1.34	3.70	29.0	.48	1.52	7.98		5.04	9.50	.73
FAGA161	11885	84.3	86.9	2.6	46	4A0	2.88	.04	.54	1.07	10.0	.27	1.69	2.09		1.61	3.78	.66
FAGA161	11886	86.9	89.0	2.1	71	4A0	2.92	.07	.58	1.35	11.0	.69	1.29	2.86		1.93	4.15	.70
FAGA161	11887	109.8	111.3	1.5	93	4A4		.03	1.95	3.40	32.0					5.35		.64
FAGA161	11888	114.7	116.7	2.0	85	4A0	2.94	.02	1.70	3.00	32.0	.69	1.33	2.49		4.70	3.82	.64
FAGA161	11889	116.7	120.0	3.3	64	4A4	2.92	.03	3.20	4.20	54.0	3.15	1.71	2.04		7.40	3.75	.57
FAGU077	11890	1.7	3.7	2.0	100	4C5		.04	.55	.38	7.0					.93		.41
FAGU077	11891	3.7	5.4	1.7	100	4L24		.06	1.30	2.30	19.0					3.60		.64
FAGU077	11892	12.0	14.2	2.2	95	4L41		.01	1.45	2.50	20.0					3.95		.63
FAGU077	11893	66.0	68.0	2.0	70	4A0	3.10	.10	.53	.92	16.0	1.10	1.63	9.70		1.45	11.33	.63
FAGU077	11894	68.0	70.1	2.1	100	4A4	3.10	.04	2.40	3.00	35.0	1.51	1.08	8.20		5.40	9.28	.56
FAGU077	11895	70.1	72.2	2.1	86	4A34	3.65	.41	.15	5.70	25.0	.82	1.83	24.50		5.85	26.33	.97
FAGU077	11896	72.2	74.8	2.6	100	4E4	4.42	.16	7.90	12.60	130.0	.89	1.16	23.00		20.50	24.16	.61
FAGU077	11897	74.8	76.2	1.4	79	4A3	3.31	.24	.65	.85	20.0	.55	1.88	18.20		1.50	20.08	.57
FAGU077	11898	76.2	78.2	2.0	100	4A3	3.39	.21	.06	.41	10.0	.82	1.20	20.80		.47	22.00	.87
FAGU077	11899	78.2	80.2	2.0	45	4A3	2.93	.34	.69	1.03	27.0	.69	1.58	25.80		1.72	27.38	.60
FAGU077	11900	80.2	82.3	2.1	100	4A3	3.53	.26	.28	.49	15.0	1.03	1.11	21.80		.77	22.91	.64
FAGU077	11901	82.3	84.2	1.9	95	4A43	3.74	.14	3.80	5.30	79.0	.48	1.18	21.80		9.10	22.98	.58
FAGU077	11902	84.2	86.6	2.4	100	4A0	3.01	.06	1.47	2.60	26.0	1.99	2.46	6.90		4.07	9.36	.64
FAGU077	11903	86.6	88.9	2.3	100	4A0	3.00	.06	1.04	1.34	17.0	2.13	2.59	6.20		2.38	8.79	.56
FAGU077	11904	90.0	91.4	1.4	43	4A3	3.10	.10	.79	1.05	18.0	1.10	1.92	11.40		1.84	13.32	.57
FAGU077	11905	91.4	94.4	3.0	93	4A0	2.95	.07	1.05	1.58	20.0	1.44	.81	6.70		2.63	7.51	.60
FAGU077	11906	94.4	97.5	3.1	84	4A0	2.92	.06	.85	1.04	18.0	.89	.78	6.10		1.89	6.88	.55
FAGU077	11907	97.5	100.4	2.9	100	4A0	2.98	.05	1.16	1.59	21.0	.75	.74	7.90		2.75	8.64	.58
FAGU077	11908	100.4	102.0	1.6	100	4A41	2.93	.03	2.90	5.20	40.0	.62	1.07	2.43		8.10	3.50	.64
FAGU077	11909	102.0	102.5	.5	100	4A3	3.19	.15	.52	1.05	16.0	1.10	.85	14.10		1.57	14.95	.67
FAGU077	11910	102.5	104.5	2.0	100	4E46	4.68	.24	4.80	5.90	82.0	1.37	1.06	28.50		10.70	29.56	.55
FAGU077	11911	104.5	106.5	2.0	100	4E46	4.73	.30	5.30	6.50	97.0	1.44	1.03	32.00		11.80	33.03	.55
FAGU077	11912	106.5	108.2	1.7	100	4E46	4.57	.18	4.70	2.70	88.0	.34	.90	35.20		7.40	36.10	.36

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAG	PS+ZN	PO+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGU077	11913	123.0	125.2	2.2	100	4E6	4.57	.11	5.40	5.90	83.0	.69	1.05	30.50		11.30	31.55	.52
FAGU077	11914	132.8	134.1	1.3	85	4E4	4.17	.10	4.80	7.50	84.0	.48	1.23	25.80		12.30	27.03	.61
FAGU077	11915	134.1	136.1	2.0	100	4A4	3.28	.07	2.70	4.40	46.0	.41	2.28	9.90		7.10	12.18	.62
FAGU077	11916	136.1	138.1	2.0	100	4A3	3.52	.21	2.50	2.10	40.0	.75	1.10	19.80		4.60	20.90	.46
FAGU077	11917	138.1	140.1	2.0	100	4A4	3.48	.11	7.50	10.00	94.0	.41	1.76	10.90		17.50	12.66	.57
FAGU077	11918	140.1	142.1	2.0	100	4A30	3.23	.12	1.10	3.50	19.0	.48	3.80	13.10		4.60	16.90	.76
FAGU077	11919	142.1	143.7	1.6	81	4A31	3.17	.20	.13	.91	10.0	.34	1.85	10.80		1.04	12.65	.88
FAGU077	11920	143.7	145.6	1.9	95	4EA	3.52	.08	4.20	5.10	57.0	1.30	1.82	16.00		9.30	17.82	.55
FAGA158	11921	17.7	20.1	2.4	58	4E4	4.28	.06	6.90	10.80	129.0	1.03	2.99	24.50		17.70	27.49	.61
FAGA158	11922	20.1	23.2	3.1	39	4D4	3.08	.02	3.00	5.80	54.0	.62	2.71	5.32		8.80	8.03	.66
FAGA158	11923	49.4	51.6	2.2	91	4D0	3.02	.01	2.20	5.50	49.0	.75	3.29	4.21		7.70	7.50	.71
FAGA158	11924	51.6	53.5	1.9	100	4D0	3.12	.02	2.60	6.50	53.0	.96	3.64	5.86		9.10	9.50	.71
FAGA158	11925	67.5	68.5	1.0	100	4D0	3.05	.01	2.50	6.90	51.0	.75	3.22	3.65		9.40	6.87	.73
FAGA158	11926	69.0	71.0	2.0	100	4DE	3.17	.02	1.98	6.00	40.0	.82	5.99	5.81		7.98	11.80	.75
FAGA158	11927	91.2	94.1	2.9	97	4AD	2.98	.03	2.10	4.80	39.0	.96	1.70	4.33		6.90	6.03	.70
FAGA158	11928	96.5	99.0	2.5	100	4A0	2.95	.01	.13	.33	4.0	.69	4.95	1.19		.46	6.14	.72
FAGA158	11929	99.0	101.8	2.8	100	4A4	3.01	.03	2.20	4.50	43.0	.27	1.51	3.68		6.70	5.19	.67
FAGA158	11930	103.2	105.1	1.9	56	4E1	3.64	.03	1.29	4.30	28.0	.48	5.64	18.20		5.59	23.84	.77
FAGA158	11931	105.1	106.6	1.5	93	4A43	3.65	.03	1.03	4.40	29.0	.48	7.94	16.70		5.43	24.64	.81
FAGA158	11932	110.8	113.0	2.2	91	4H1	3.77	.18	4.60	6.00	92.0	.34	15.63	11.90		10.60	27.53	.57
FAGA158	11933	113.0	114.7	1.7	94	4AE	3.90	.22	7.50	12.20	158.0	.55	2.79	17.30		19.70	20.09	.62
FAGA158	11934	115.8	117.2	1.4	100	4A4	3.25	.03	2.20	3.70	42.0	.69	1.47	8.70		5.90	10.17	.63
FAGA158	11935	118.3	119.8	1.5	100	4A4	3.34	.04	3.30	5.40	52.0	1.03	2.35	9.70		8.70	12.05	.62
FAGA158	11936	119.8	121.0	1.2	100	4L0	3.56	.11	3.10	4.80	55.0	1.51	3.47	16.90		7.90	20.37	.61
FAGA158	11937	121.0	123.3	2.3	61	4AD	3.69	.09	4.30	8.40	83.0	1.44	5.23	14.90		12.70	20.13	.66
FAGA158	11938	125.7	128.7	3.0	80	4A4	3.41	.04	4.90	9.50	96.0	1.44	2.30	10.50		14.40	12.80	.66
FAGA158	11939	128.7	131.6	2.9	100	4A4	3.08	.03	1.89	4.40	29.0	.69	4.60	4.80		6.29	9.40	.70
FAGU075	11940	.0	1.7	1.7	100	4A30		.13	1.17	1.41	26.0					2.58		.55
FAGU075	11941	4.8	7.1	2.3	96	4C5		.03	1.02	1.34	12.0					2.36		.57
FAGU075	11942	7.1	8.5	1.4	100	4L14		.03	1.16	1.77	15.0					2.93		.60
FAGU075	11943	12.1	13.4	1.3	92	4L41		.02	2.30	2.90	31.0					5.20		.56
FAGU075	11944	22.2	24.6	2.4	92	4L4		.03	.34	.80	7.0					1.14		.70
FAGU075	11945	26.3	29.0	2.7	100	4L4		.03	1.07	.21	14.0					1.28		.16
FAGU075	11946	39.7	41.0	1.3	92	4L4		.05	.24	.30	4.0					.54		.56
FAGU075	11947	41.0	43.8	2.8	96	4AG		.09	.37	1.00	10.0					1.37		.73
FAGU075	11948	48.4	50.9	2.5	76	4A0	3.04	.09	2.01	2.80	41.0	1.03	.89	8.70		4.81	9.59	.58
FAGU075	11949	50.9	53.8	2.9	86	4A3	3.67	.25	.14	.39	16.0	1.23	1.36	25.30		.53	26.66	.74
FAGU075	11950	53.8	56.7	2.9	100	4E4	4.49	.18	4.80	8.40	107.0	.62	.81	20.70		13.20	21.51	.64
FAGU075	11951	56.7	57.5	.8	75	5D4\$	3.07	.02	1.34	.98	25.0	.48	2.40	6.90		2.32	9.30	.42
FAGU075	11952	57.5	59.0	1.5	93	4E4	4.60	.20	2.90	5.00	58.0	2.67	.81	30.30		7.90	31.11	.63
FAGU075	11953	59.0	61.0	2.0	85	4E4	4.66	.17	3.30	4.70	73.0	1.65	.79	34.40		8.00	35.19	.59
FAGU075	11954	61.0	61.4	.4	75	5D4\$	3.10	.02	1.52	3.70	30.0	.48	1.52	7.50		5.22	9.02	.71
FAGU075	11955	61.4	63.4	2.0	90	4G4	4.70	.16	9.00	10.10	156.0	1.92	.63	20.80		19.10	21.43	.53
FAGU075	11956	63.4	65.4	2.0	90	4G4	4.24	.09	5.20	8.90	95.0	1.71	.72	18.80		14.10	19.52	.63
FAGU075	11957	65.4	67.4	2.0	75	4G4	4.73	.15	4.40	8.80	96.0	1.85	.70	21.60		13.20	22.30	.67
FAGU075	11958	67.4	69.4	2.0	100	4G0	4.64	.07	2.10	4.00	94.0	1.51	.70	18.10		6.10	18.80	.66
FAGU075	11959	69.4	71.4	2.0	95	4G4	4.67	.13	3.50	7.20	79.0	2.06	.40	18.50		10.70	18.90	.67
FAGU075	11960	71.4	73.0	1.6	81	4G4	4.64	.10	4.50	7.60	80.0	1.03	.57	24.10		12.10	24.67	.63
FAGU075	11961	73.0	74.5	1.5	93	4G4	4.56	.13	4.30	7.70	84.0	1.92	.91	17.50		12.00	18.41	.64
FAGU075	11962	127.6	129.2	1.6	87	4D4	3.69	.04	4.70	10.80	83.0	1.44	1.54	14.60		15.50	16.14	.70

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAO	PB+ZN	PO+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGU075	11963	129.2	131.0	1.8	89	4E4	4.33	.35	2.60	4.60	50.0	2.26	1.31	32.10		7.20	33.41	.64
FAGU075	11964	131.0	133.1	2.1	76	4A3	3.52	.37	1.22	2.50	34.0	1.37	2.37	20.10		3.72	22.47	.67
FAGU075	11965	147.8	149.9	2.1	100	4L		.16	.60	.76	14.0					1.36		.56
FAGU075	11966	165.8	169.0	3.2	78	4A0		.11	1.66	1.59	23.0					3.25		.49
FAGA080	11967	264.9	266.7	1.8	94	4A0	2.98	.04	.51	1.55	10.0	.14	6.02	6.00		2.06	12.02	.75
FAGA080	11968	266.7	268.2	1.5	100	4A0	2.98	.04	1.01	2.00	20.0	.21	3.69	6.00		3.01	9.69	.66
FAGA080	11969	268.2	270.1	1.9	95	4A0	2.93	.03	.98	1.84	18.0	.27	2.43	5.80		2.82	8.23	.65
FAGU091	11970	.0	3.0	3.0	50	4A30	3.62	.09	1.94	2.70	46.0	1.17	.84	21.80		4.64	22.64	.58
FAGU091	11971	3.0	5.5	2.5	100	4A30	3.28	.04	1.13	2.60	28.0	.75	.97	13.60		3.73	14.57	.70
FAGU091	11972	5.5	8.0	2.5	96	4A34	3.41	.03	2.00	3.70	45.0	.96	1.37	15.20		5.70	16.57	.65
FAGU091	11973	8.0	10.0	2.0	95	4A1	3.01	.02	1.68	3.10	33.0	.89	1.74	6.00		4.78	7.74	.65
FAGU091	11974	10.0	12.0	2.0	100	4A14	2.98	.04	2.10	3.30	39.0	1.23	.80	5.40		5.40	6.20	.61
FAGU091	11975	12.0	14.0	2.0	95	4A14	2.97	.03	2.10	4.30	35.0	.69	.96	3.48		6.40	4.44	.67
FAGU091	11976	14.0	16.0	2.0	100	4A1	2.89	.02	1.24	2.40	20.0	1.10	.95	.77		3.64	1.72	.66
FAGU091	11977	16.0	17.4	1.4	100	4A1	2.85	.03	.46	1.27	8.0	.34	.68	.21		1.73	.89	.73
FAGU091	11978	17.4	19.4	2.0	100	4D5	3.07	.06	3.30	4.20	54.0	1.23	1.06	6.20		7.50	7.26	.56
FAGU091	11979	19.4	21.4	2.0	100	4D5	2.85	.02	1.60	3.40	26.0	.62	.82	.84		5.00	1.66	.68
FAGU091	11980	21.4	23.3	1.9	100	4C5	2.84	.02	1.57	3.40	24.0	.62	.98	4.10		4.97	5.08	.68
FAGU091	11981	23.3	26.0	2.7	100	4C5	2.83	.02	.55	.62	10.0	.55	.80	.54		1.17	1.34	.53
FAGU091	11982	26.0	29.0	3.0	40	4L41	2.88	.03	1.08	2.30	18.0	.48	.96	1.50		3.38	2.46	.68
FAGU091	11983	29.0	32.0	3.0	90	4L41	2.95	.07	1.83	1.76	32.0	1.30	.84	5.29		3.59	6.13	.49
FAGU091	11984	32.0	35.0	3.0	97	4L41	2.96	.07	1.30	1.06	25.0	.96	1.01	5.94		2.36	6.95	.45
FAGU091	11985	35.0	37.5	2.5	100	4L41	2.84	.03	.58	1.72	10.0	.55	.85			2.30	.85	.75
FAGU091	11986	37.5	41.5	4.0	60	4C0	2.92	.03	1.31	1.71	23.0	.62	.94	4.58		3.02	5.52	.57
FAGU091	11987	41.5	42.7	1.2	83	4L41	2.92	.07	1.34	2.70	30.0	.64	1.91	3.20		4.04	5.11	.67
FAGU091	11988	62.6	65.1	2.5	92	4AE4	3.63	.22	3.00	4.90	48.0	1.71	1.56	19.80		7.90	21.36	.62
FAGU091	11989	65.1	67.6	2.5	84	4AE4	3.50	.13	2.10	3.90	39.0	1.78	1.37	21.40		6.00	22.77	.65
FAGU091	11990	67.6	70.0	2.4	100	4A0	2.89	.04	.69	1.03	16.0	.48	.59	1.80		1.72	2.39	.60
FAGU091	11991	70.0	72.0	2.0	95	4A0		.04	.64	.63	3.0					1.27		.50
FAGU091	11992	72.0	75.0	3.0	23	4A0		.07	.64	1.20	16.0					1.84		.65
FAGU091	11993	75.0	77.7	2.7	100	4L42		.08	.66	.92	16.0					1.58		.58
FAGU091	11994	79.1	81.4	2.3	91	4C0		.07	.45	.85	12.0					1.30		.65
FAGU091	11995	81.4	83.3	1.9	89	4L42	2.93	.08	.70	1.84	9.0	.34	.51	6.30		2.54	6.81	.72
FAGU091	11996	83.3	86.9	3.6	97	4L42	2.86	.03	3.10	1.43	35.0	.48	2.86	1.00		4.53	3.86	.32
FAGU091	11997	86.9	91.4	4.5	56	4L42		.04	.61	.88	11.0					1.49		.59
FAGU091	11998	91.4	94.4	3.0	93	4L42		.04	.46	.57	3.0					1.03		.55
FAGU091	11999	94.4	97.5	3.1	100	4A34	3.09	.10	2.10	3.00	30.0	.48	9.60	.61		5.10	10.21	.59
FAGU093	12035	.0	3.0	3.0	53	4A3	3.62	.11	1.53	2.90	37.0	1.10	1.69	22.10		4.43	23.79	.65
FAGU093	12036	3.0	5.0	2.0	85	4A14	3.34	.05	2.80	5.00	55.0	.96	1.69	24.70		7.80	26.39	.64
FAGU093	12037	5.0	7.1	2.1	57	4A14	3.54	.12	2.10	4.10	47.0	1.03	1.42	8.30		6.20	9.72	.66
FAGU093	12038	7.1	9.6	2.5	92	4D5	3.41	.05	2.80	4.20	49.0	.89	1.19	20.20		7.00	21.39	.60
FAGU093	12039	9.6	12.2	2.6	100	4D5	3.38	.05	2.70	3.90	46.0	1.10	1.57	15.20		6.60	16.77	.59
FAGU093	12040	12.2	14.2	2.0	100	4C5	3.44	.07	1.74	3.00	28.0	.82	1.11	16.40		4.74	17.51	.63
FAGU093	12041	14.2	15.9	1.7	100	4C5	2.95	.03	1.25	3.10	16.0	.34	.72	18.30		4.35	19.02	.71
FAGU093	12042	15.9	18.0	2.1	86	4C0	3.01	.04	1.27	3.50	26.0	.55	.92	4.34		4.77	5.26	.73
FAGU093	12043	18.0	19.8	1.8	100	4AG	2.86	.03	1.57	3.30	26.0	.41	.86	5.18		4.87	6.04	.68
FAGU093	12044	19.8	22.8	3.0	93	4C5	2.87	.06	1.70	3.30	27.0	.82	.84	1.50		5.00	2.34	.66
FAGU093	12045	22.8	24.8	2.0	100	4C0	3.04	.08	1.12	1.15	24.0	1.23	.93	2.08		2.27	3.01	.51
FAGU093	12046	24.8	26.3	1.5	100	4C0	2.91	.05	1.54	2.50	27.0	.62	.82	8.40		4.04	9.22	.62
FAGU093	12047	26.3	27.4	1.1	91	4L12	2.96	.06	1.57	1.88	26.0	1.17	.79	3.56		3.45	4.35	.54

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAO	PB+ZN	PO+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGU093	12048	43.9	46.7	2.8	89	4A4	3.28	.07	3.20	5.70	48.0	1.03	2.02	4.42		8.90	6.44	.64
FAGU093	12049	46.7	48.8	2.1	95	4L4	2.96	.05	2.03	3.90	35.0	.48	3.46	8.10		5.93	11.56	.66
FAGU093	12050	48.8	49.6	.8	100	4D0	2.87	.02	2.15	5.40	34.0	.41	1.50	12.70		7.55	14.20	.72
FAGU093	12051	49.6	52.3	2.7	48	4L14	2.86	.03	1.00	2.60	23.0	.55	.98	5.66		3.60	6.64	.72
FAGU093	12052	52.3	54.3	2.0	100	4L14	3.03	.09	.70	1.55	10.0	1.10	1.36	2.01		2.25	3.37	.69
FAGU093	12053	54.3	57.0	2.7	96	4L21	2.95	.07	.53	1.00	12.0	.48	2.12	6.60		1.53	8.72	.65
FAGU093	12054	57.0	59.5	2.5	76	4B0	2.90	.05	1.67	1.21	21.0	.34	2.16	4.77		2.88	6.93	.42
FAGU093	12055	59.5	61.5	2.0	80	4A0	3.12	.03	1.10	2.80	28.0	.82	1.63	2.05		3.90	3.68	.72
FAGU093	12056	61.5	63.1	1.6	88	4A0	3.28	.05	1.45	2.60	30.0	.96	1.31	10.10		4.05	11.41	.64
FAGU093	12057	63.1	64.8	1.7	94	4A4	3.36	.09	2.05	4.70	37.0	1.30	1.41	15.20		6.75	16.61	.70
FAGU093	12058	64.8	65.7	.9	100	4A4	3.43	.10	3.70	6.60	67.0	1.78	1.82	14.90		10.30	16.72	.64
FAGU093	12059	65.7	67.1	1.4	79	4E41	3.13	.14	7.10	13.50	108.0	1.85	2.03	10.80		20.60	12.83	.66
FAGU097	12060	.0	3.0	3.0	47	4A34	3.45	.04	3.20	6.00	68.0	.89	1.49	19.10		9.20	20.59	.65
FAGU097	12061	3.0	4.6	1.6	62	4A34	3.63	.07	3.30	4.80	60.0	1.30	1.62	14.90		8.10	16.52	.59
FAGU097	12062	4.6	6.6	2.0	100	4A43	3.36	.04	2.90	3.60	50.0	1.03	1.10	19.30		6.50	20.40	.55
FAGU097	12063	6.6	8.6	2.0	90	4A43	3.24	.03	1.90	4.30	44.0	.41	1.10	15.70		6.20	16.80	.69
FAGU097	12064	8.6	10.6	2.0	95	4A3	3.39	.02	1.10	2.80	30.0	.89	1.37	11.30		3.90	12.67	.72
FAGU097	12065	10.6	12.6	2.0	70	4A3	3.14	.03	1.29	2.90	28.0	.55	1.15	17.30		4.19	18.45	.69
FAGU097	12066	12.6	14.6	2.0	80	4A43	3.16	.02	1.19	4.60	29.0	.55	1.40	9.80		5.79	11.20	.79
FAGU097	12067	14.6	16.6	2.0	95	4A3	3.51	.02	.85	4.00	26.0	.62	1.44	16.80		4.85	18.24	.82
FAGU097	12068	16.6	18.6	2.0	80	4A43	3.24	.02	2.30	5.00	35.0	.75	1.34	10.70		7.30	12.04	.69
FAGU097	12069	18.6	21.3	2.7	30	4A34	3.47	.02	1.87	6.10	40.0	.75	1.38	14.60		7.97	15.98	.77
FAGU097	12070	21.3	23.3	2.0	75	4A4	3.24	.02	1.10	4.40	30.0	.55	1.45	24.40		5.50	25.85	.80
FAGU097	12071	23.3	25.3	2.0	85	4A4	3.26	.02	1.14	3.90	32.0	.82	1.20	12.70		5.04	13.90	.77
FAGU097	12072	25.3	27.3	2.0	95	4A4	3.23	.02	2.10	5.80	55.0	.82	1.37	10.70		7.90	12.07	.73
FAGU097	12073	27.3	29.3	2.0	70	4A0	3.05	.02	1.51	3.20	40.0	.62	1.56	7.40		4.71	8.96	.68
FAGU097	12074	29.3	31.3	2.0	55	4A4	3.23	.03	2.60	5.40	67.0	.82	1.40	10.40		8.00	11.80	.68
FAGU097	12075	31.3	33.3	2.0	100	4A4	2.95	.02	1.80	4.20	44.0	.62	1.26	4.11		6.00	5.37	.70
FAGU097	12076	33.3	35.3	2.0	80	4A4	2.96	.01	3.00	5.80	62.0	.75	1.36	2.23		8.80	3.59	.66
FAGU097	12077	35.3	37.0	1.7	82	4A4	2.95	.02	2.02	3.90	47.0	.69	1.20	3.15		5.92	4.35	.66
FAGU097	12078	37.0	39.6	2.6	100	4D5	3.04	.02	2.40	6.10	55.0	.62	1.45	5.08		8.50	6.53	.72
FAGU097	12079	39.6	42.3	2.7	78	4D5	3.14	.03	3.30	6.50	71.0	.69	1.45	6.54		9.80	7.99	.66
FAGU097	12080	42.3	44.7	2.4	46	4E4	4.17	.05	4.10	12.90	74.0	1.30	4.92	19.60		17.00	24.52	.76
FAGU097	12081	44.7	46.7	2.0	70	4A30	3.38	.11	1.11	2.90	30.0	1.58	2.36	15.20		4.01	17.56	.72
FAGU097	12082	46.7	48.4	1.7	88	4A34	3.47	.12	1.94	4.00	35.0	1.58	2.79	14.60		5.94	17.39	.67
FAGU066	12083	.0	2.0	2.0	80	4E42	4.34	.24	9.30	14.80	136.0	2.95	2.08	19.90		24.10	21.98	.61
FAGU066	12084	2.0	3.4	1.4	71	4E42	4.69	.18	7.20	17.00	98.0	1.71	3.18	24.40		24.20	27.58	.70
FAGU066	12085	3.4	5.4	2.0	100	4E4	4.91	.24	4.30	8.00	69.0	2.88	1.34	34.70		12.30	36.04	.65
FAGU066	12086	5.4	7.3	1.9	84	4E4	4.76	.20	6.60	10.90	76.0	2.19	1.63	30.60		17.50	32.23	.62
FAGU066	12087	7.3	9.3	2.0	100	4EG4	4.78	.21	6.20	9.40	121.0	2.33	.74	19.30		15.60	20.04	.60
FAGU066	12088	9.3	11.4	2.1	81	4EG4	4.86	.16	5.70	9.90	117.0	2.19	1.46	21.80		15.60	23.26	.63
FAGU066	12089	11.4	13.9	2.5	80	4G4	4.75	.10	3.90	8.70	83.0	1.23	.59	14.60		12.60	15.19	.69
FAGU066	12090	13.9	15.9	2.0	70	4EG4	4.75	.14	6.70	10.90	122.0	1.37	.75	34.50		17.60	35.25	.62
FAGU066	12091	15.9	16.7	.8	100	4AL0	3.27	.07	1.30	2.50	34.0	.48	1.23	11.60		3.80	12.83	.66
FAGU066	12092	16.7	18.4	1.7	41	4EA4	3.58	.09	2.90	4.10	49.0	.55	2.87	16.00		7.00	18.87	.59
FAGU066	12093	18.4	19.4	1.0	90	5D40	3.08	.04	.38	.59	8.0	.34	5.09	5.90		.97	10.99	.61
FAGU066	12094	19.4	20.5	1.1	82	4E4	4.47	.10	9.00	12.70	126.0	1.10	1.78	21.80		21.70	23.58	.59
FAGU066	12095	20.5	22.0	1.5	100	4EG4	4.73	.12	8.40	17.50	117.0	1.44	1.63	22.90		25.90	24.53	.68
FAGU066	12096	22.0	23.4	1.4	93	4G4	4.86	.19	5.60	9.70	98.0	1.30	1.01	22.50		15.30	23.51	.63
FAGU066	12097	23.4	25.9	2.5	100	4E4	4.60	.20	6.80	19.40	109.0	1.23	2.11	23.00		26.20	25.11	.74

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAO	PB+ZN	PO+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGU066	12098	39.2	41.3	2.1	71	4E4	4.51	.18	4.40	4.50	72.0	.69	3.33	30.60		8.90	33.93	.51
FAGU066	12099	41.3	45.7	4.4	95	4L2	3.45	.10	1.40	1.37	32.0	.69	5.74	12.50		2.77	18.24	.49
FAGU066	12100	47.2	48.7	1.5	73	4E8		.18	2.50	1.93	37.0					4.43		.44
FAGU066	12101	71.6	72.6	1.0	100	4E0	4.20	.30	2.01	.48	49.0	.27	4.27	20.30		2.49	24.57	.19
FAGU066	12102	72.6	73.3	.7	71	4L0	3.11	.08	.53	.19	22.0	.21	1.26	8.40		.72	9.66	.26
FAGU066	12103	73.3	76.1	2.8	71	4E4	4.39	.12	2.40	3.10	62.0	.55	2.53	30.20		5.50	32.73	.56
FAGU066	12104	76.1	78.5	2.4	96	4G4#	4.45	.11	5.70	6.20	105.0	.82	1.60	17.20		11.90	18.80	.52
FAGU066	12105	78.5	80.7	2.2	100	4G4	4.53	.06	6.00	8.10	91.0	1.17	1.94	7.40		14.10	9.34	.57
FAGU066	12106	80.7	83.2	2.5	80	4G4#	4.28	.13	6.80	7.10	117.0	.96	2.42	20.90		13.90	23.32	.51
FAGU066	12107	83.2	85.5	2.3	48	4LEG	3.39	.23	1.00	.74	30.0	.62	4.67	13.40		1.74	18.07	.43
FAGU066	12108	85.5	86.8	1.3	100	4G0#	3.32	.12	3.90	3.90	95.0	.69	2.78	23.60		7.80	26.38	.50
FAGU066	12109	86.8	87.5	.7	86	4L2	3.45	.21	1.90	.86	41.0	.48	3.11	16.30		2.76	19.41	.31
FAGU066	12110	87.5	88.8	1.3	100	4G4#	4.14	.10	6.20	6.50	80.0	.82	2.22	22.50		12.70	24.72	.51
FAGU066	12111	88.8	89.5	.7	71	4L3	3.12	.75	.35	.46	39.0	.62	3.85	2.69		.81	6.54	.57
FAGU066	12112	89.5	91.3	1.8	100	4G4	4.63	.06	5.70	8.70	100.0	.55	2.64	7.30		14.40	9.94	.60
FAGU066	12113	91.3	93.1	1.8	22	4G4	4.64	.05	6.40	7.60	105.0	.55	1.75	7.60		14.00	9.35	.54
FAGU066	12114	93.1	95.0	1.9	100	5D4*	3.11	.08	.91	.85	23.0	.27	3.35	6.20		1.76	9.55	.48
FAGU066	12115	95.0	98.7	3.7	73	4GE4	4.61	.06	5.90	8.50	108.0	.34	1.73	8.30		14.40	10.03	.59
FAGU101	12116	.0	2.7	2.7	19	4D4	3.65	.04	5.60	7.90	94.0	.82	4.34	12.40		13.50	16.74	.59
FAGU101	12117	2.7	4.2	1.5	100	4D0	3.43	.03	2.30	5.50	52.0	.55	2.25	8.70		7.80	10.95	.71
FAGU101	12118	54.9	55.8	.9	89	4GE4	3.84	.08	9.50	17.60	166.0	1.03	2.36	6.90		27.10	9.26	.65
FAGU101	12119	55.8	58.0	2.2	91	4A43	3.22	.07	2.80	3.60	57.0	1.03	3.15	6.40		6.40	9.55	.56
FAGU101	12120	58.0	60.5	2.5	100	5D4@	3.46	.06	3.80	3.30	57.0	1.10	2.96	11.10		7.10	14.06	.46
FAGU101	12121	60.5	63.1	2.6	100	5D4@	3.34	.05	3.30	3.70	56.0	.75	3.27	8.00		7.00	11.27	.53
FAGU101	12122	63.1	65.6	2.5	100	4A4	3.50	.04	4.40	5.30	73.0	1.10	1.89	12.40		9.70	14.29	.55
FAGU101	12123	67.7	69.2	1.5	87	4AD	3.14	.03	2.30	3.60	38.0	.62	2.01	6.30		5.90	8.31	.61
FAGU101	12124	69.2	70.6	1.4	100	4A0	2.96	.02	.97	2.50	25.0	.41	1.91	2.46		3.47	4.37	.72
FAGU101	12125	70.6	72.3	1.7	100	4A41	3.42	.04	3.10	3.60	53.0	.89	2.27	11.80		6.70	14.07	.54
FAGU101	12126	72.3	74.0	1.7	76	4A1	3.35	.03	1.57	2.30	31.0	.75	3.55	9.60		3.87	13.15	.59
FAGU101	12127	74.0	76.8	2.8	71	4AD	2.99	.01	.55	1.89	10.0	.21	2.83	2.07		2.44	4.90	.77
FAGU101	12128	76.8	79.3	2.5	92	4A0	2.95	.01	.84	2.30	20.0	.27	2.49	2.31		3.14	4.80	.73
FAGU101	12129	79.3	80.8	1.5	87	5A94	2.93	.01	1.66	3.70	36.0	.62	2.19	1.60		5.36	3.79	.69
FAGU101	12130	80.8	82.1	1.3	100	4A0	2.93	.01	.87	1.98	19.0	.62	2.20	4.60		2.85	6.80	.69
FAGU101	12131	82.1	84.5	2.4	100	5B6	2.93	.01	.55	.64	11.0	.55	2.22	4.10		1.19	6.32	.54
FAGU101	12132	84.5	86.8	2.3	100	4A31	3.02	.03	1.59	2.80	32.0	.96	1.07	5.70		4.39	6.77	.64
FAGU101	12133	86.8	88.9	2.1	100	5B62		.01	.04	.07	1.0					.11		.64
FAGU101	12134	88.9	90.6	1.7	100	5A6	2.94	.01	.77	1.26	19.0	.14	2.34	2.56		2.03	4.90	.62
FAGU101	12135	90.6	93.6	3.0	97	4AG3	3.14	.04	1.39	2.60	30.0	.82	1.09	10.40		3.99	11.49	.65
FAGU101	12136	93.6	95.2	1.6	100	5B6		.01	.09	.12	3.0					.21		.57
FAGU101	12137	95.2	98.1	2.9	83	5B6		.01	.61	.90	11.0					1.51		.60
FAGU101	12138	98.1	99.1	1.0	70	4E4*	4.28	.15	6.80	12.40	130.0	1.65	1.44	23.50		19.20	24.94	.65
FAGU101	12139	131.1	133.9	2.8	96	4A0		.07	.10	.18	4.0					.28		.64
FAGU101	12140	133.9	134.8	.9	89	4AC	3.00	.10	.03	.05	5.0	.27	4.77	6.80		.08	11.57	.63
FAGU101	12141	134.8	137.3	2.5	96	4A0		.07	.04	.11	2.0					.15		.73
FAGU101	12142	137.3	138.7	1.4	100	4A0		.06	.73	1.52	14.0					2.25		.68
FAGU101	12143	138.7	140.0	1.3	92	4A0		.12	.05	.10	5.0					.15		.67
FAGU101	12144	140.0	142.0	2.0	100	4AC0		.12	.07	.22	5.0					.29		.76
FAGU101	12145	142.0	143.4	1.4	86	5D\$		.01	.03	.07	3.0					.10		.71
FAGU101	12146	143.4	145.7	2.3	74	4A4	3.24	.06	1.95	3.20	36.0	1.03	1.67	11.60		5.15	13.27	.62
FAGU101	12147	145.7	147.8	2.1	90	4G45	3.65	.05	3.40	7.50	63.0	1.10	1.59	17.00		10.90	18.59	.69

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAO	PB+ZN	PC+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGU101	12148	147.8	149.0	1.2	100	4A0	3.10	.02	1.26	3.00	26.0	.48	2.56	6.80		4.26	9.36	.70
FAGU103	12149	.0	2.4	2.4	50	4A4	3.72	.02	5.20	9.40	97.0	2.06	2.89	14.70		14.60	17.59	.64
FAGU103	12150	2.4	4.6	2.2	55	5D4a	3.04	.02	1.96	3.90	34.0	.27	4.90	3.64		5.86	8.54	.67
FAGU099	12151	.0	1.3	1.3		4A4	3.10	.02	1.91	3.60	42.0	.48	2.88	5.77		5.51	8.65	.65
FAGU099	12152	1.3	3.9	2.6		4D4	3.20	.02	4.00	8.70	63.0	.75	1.75	7.10		12.70	8.85	.69
FAGU099	12153	3.9	5.6	1.7		4D4	3.29	.08	3.20	8.40	84.0	1.17	1.40	10.30		11.60	11.70	.72
FAGU099	12154	5.6	7.5	1.9		4D4	3.32	.02	1.97	4.50	38.0	.48	2.66	10.80		6.47	13.46	.70
FAGU099	12155	114.3	116.8	2.5		4E4	4.28	.13	4.80	9.00	96.0	1.65	1.97	26.40		13.80	28.37	.65
FAGU099	12156	116.8	119.1	2.3		4E4	4.63	.18	5.10	7.20	95.0	1.78	1.34	32.40		12.30	33.74	.59
FAGU099	12157	119.1	121.2	2.1		4E4	4.42	.16	5.20	8.50	102.0	1.44	1.29	30.50		13.70	31.79	.62
FAGU099	12158	121.2	123.7	2.5		4A4	3.26	.08	2.90	3.50	45.0	1.03	2.14	12.80		6.40	14.94	.55
FAGU099	12159	123.7	126.5	2.8		4A0	3.13	.09	1.25	2.60	23.0	.89	2.93	11.60		3.85	14.53	.68
FAGU099	12160	132.8	134.8	2.0		4A0		.15	.50	.62	20.0					1.12		.55
FAGUC99	12161	134.8	138.7	3.9		4A0		.13	.15	.41	14.0					.56		.73
FAGU099	12162	138.7	142.3	3.6		4A0		.11	.40	.48	14.0					.88		.54
FAGU099	12163	142.3	145.3	3.0		4A0		.13	.11	.48	11.0					.59		.81
FAGU099	12164	145.3	147.0	1.7		4A0		.19	.24	.61	13.0					.85		.72
FAGU099	12165	147.0	148.9	1.9		4AC		.28	.21	.43	15.0					.64		.67
FAGU099	12166	151.4	152.3	.9		4A0	3.25	.13	1.18	.94	23.0	1.51	3.39	14.10		2.12	17.49	.44
FAGU099	12167	152.3	153.2	.9		4E4	3.83	.10	3.70	4.80	78.0	1.44	2.21	23.10		8.50	25.31	.56
FAGU095	12168	.0	3.8	3.8	42	4A4	3.10	.06	3.20	4.30	55.0	.62	1.59	7.00		7.50	8.59	.57
FAGU095	12169	3.8	6.7	2.9		4A43	3.36	.06	3.80	4.90	72.0	1.03	1.69	14.00		8.70	15.69	.56
FAGU095	12170	6.7	9.1	2.4		4A43	3.24	.04	2.40	5.20	48.0	.75	1.70	12.90		7.60	14.60	.68
FAGU095	12171	9.1	12.0	2.9		4A43	3.15	.04	1.60	4.00	34.0	.69	1.51	12.20		5.60	13.71	.71
FAGU095	12172	12.0	14.6	2.6		4A43	3.24	.04	3.90	7.30	72.0	.75	1.58	10.70		11.20	12.28	.65
FAGU095	12173	14.6	15.4	.8		4D45	3.32	.02	6.90	11.50	138.0	.96	2.22	9.30		18.40	11.52	.63
FAGU095	12174	15.4	17.2	1.8		4A3	3.29	.04	1.47	3.20	33.0	.75	1.85	11.90		4.67	13.75	.69
FAGU095	12175	17.2	19.6	2.4		4A43	3.34	.06	1.74	3.60	38.0	1.23	1.28	15.10		5.34	16.38	.67
FAGU095	12176	19.6	20.5	.9		4L3	2.82	.02	.36	.62	10.0	.27	1.86	3.59		.98	5.45	.63
FAGU095	12177	20.5	22.3	1.8		4E4	3.84	.03	6.30	10.00	116.0	1.92	1.84	14.30		16.30	16.14	.61
FAGU095	12178	22.3	24.0	1.7		4E41	3.75	.03	6.50	9.10	105.0	1.10	2.54	18.30		15.60	20.84	.58
FAGU095	12179	24.0	25.5	1.5		4A0	2.93	.01	.27	.29	8.0	.34	.84	5.30		.56	6.14	.52
FAGU095	12180	25.5	27.7	2.2		4G4	3.61	.05	2.80	8.60	58.0	.41	1.32	17.10		11.40	18.42	.75
FAGU095	12181	27.7	28.6	.9		4L3	3.43	.01	.33	1.00	12.0	.55	1.83	15.00		1.33	16.83	.75
FAGU095	12182	28.6	30.7	2.1		4G0	3.62	.01	1.84	6.30	40.0	.48	2.31	19.10		8.14	21.41	.77
FAGU095	12183	30.7	32.0	1.3		4A0	2.88	.01	.83	1.85	18.0	.48	1.79	4.19		2.68	5.98	.69
FAGU095	12184	38.3	41.1	2.8		4EK4	3.82	.04	5.40	13.90	94.0	1.10	2.13	17.80		19.30	19.93	.72
FAGU095	12185	41.1	42.9	1.8		4AD4	3.39	.08	5.40	12.80	94.0	1.58	3.13	11.70		18.20	14.83	.70
FAGU095	12186	42.9	45.2	2.3		4A34	3.32	.08	4.80	7.20	78.0	1.99	2.21	11.80		12.00	14.01	.60
FAGU095	12187	45.2	47.2	2.0		4AD	3.53	.15	3.00	4.00	50.0	3.50	2.47	15.20		7.00	17.67	.57
FAGU095	12188	50.3	52.6	2.3		4A43	3.39	.10	2.80	4.20	50.0	1.44	2.15	18.60		7.00	20.75	.60
FAGU095	12189	52.6	54.9	2.3		4A43	2.97	.05	2.70	3.20	43.0	.89	2.07	7.80		5.90	9.87	.54
FAGU095	12190	110.5	113.0	2.5		4A0	3.12	.08	.16	.40	10.0	.69	1.98	12.60		.56	14.58	.71
FAGU095	12191	113.0	115.2	2.2		4A0	2.92	.05	1.57	2.30	35.0	.82	2.09	7.80		3.87	9.89	.59
FAGU095	12192	115.2	117.2	2.0		4E46	4.38	.20	5.90	8.30	103.0	1.65	1.77	28.20		14.20	29.97	.58
FAGU095	12193	117.2	119.3	2.1		4E46	4.45	.18	4.40	5.10	95.0	1.44	1.19	34.40		9.50	35.59	.54
FAGU105	12194	.0	3.8	3.8	79	4K0	3.10	.02	.52	1.25	14.0	.07	7.80	5.40		1.77	13.20	.71
FAGU105	12195	3.8	5.8	2.0	80	5D4a	3.45	.01	.67	1.36	21.0	.21	5.70	15.00		2.03	20.70	.67
FAGU109	12196	.0	3.0	3.0	50	4A4	3.23	.02	1.66	4.60	44.0	.34	2.53	10.80		6.26	13.33	.73
FAGU109	12197	3.0	4.6	1.6	75	4A4	3.47	.02	4.80	12.20	128.0	.96	3.18	10.00		17.00	13.18	.72

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	FY	BAO	PB+ZN	PO+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGU109	12198	50.9	53.3	2.4	100	4A43	3.59	.05	4.80	8.80	89.0	.96	1.97	15.80		13.60	17.77	.65
FAGU109	12199	67.3	69.2	1.9	89	4D0	3.32	.10	2.40	4.10	50.0	1.51	2.20	12.60		6.50	14.80	.63
FAGU109	12200	69.2	71.2	2.0	90	4ECA	3.42	.10	2.70	3.50	52.0	1.30	4.03	16.20		6.20	20.23	.56
FAGU109	12201	71.2	73.2	2.0	95	4D0	2.93	.02	1.77	4.20	34.0	.69	2.87	3.48		5.97	6.35	.70
FAGU109	12202	73.2	74.8	1.6	94	5D*	2.94	.01	.26	.38	11.0	.21	4.99	1.47		.64	6.46	.59
FAGU109	12203	74.8	76.7	1.9	89	4A43	3.45	.12	2.80	4.80	53.0	1.67	1.66	17.00		7.60	18.66	.63
FAGU109	12204	76.7	78.3	1.6	100	4E4	4.18	.16	5.50	11.00	113.0	2.40	2.63	24.40		16.50	27.03	.67
FAGU109	12205	78.3	79.7	1.4	79	4L25	3.21	.06	1.22	2.50	36.0	.34	5.36	6.30		3.72	11.66	.67
FAGU109	12206	90.8	91.7	.9	89	4D0	2.92	.03	2.80	2.40	47.0	.27	3.73	2.94		5.20	6.67	.46
FAGU109	12207	91.7	92.6	.9	89	5D\$	2.88	.01	.03	.28	8.0	.48	5.40	.95		.31	6.35	.91
FAGU109	12208	92.6	95.5	2.9	86	4D0	2.90	.03	1.71	3.80	37.0	.69	3.79	2.35		5.51	6.14	.69
FAGU109	12209	95.5	97.3	1.8	100	4D0	2.93	.06	2.20	4.20	49.0	.82	2.65	3.28		6.40	5.93	.66
FAGU109	12210	97.3	98.7	1.4	79	5D4\$	2.88	.01	.06	.38	8.0	.14	6.70	.62		.44	7.32	.87
FAGU073	12211	.0	3.0	3.0	60	4A0	3.05	.09	2.10	1.50	38.0	.82	.90	9.20		3.60	10.10	.42
FAGU073	12212	3.0	5.5	2.5	100	4A0	3.04	.06	1.67	1.30	29.0	.75	.55	7.80		2.97	8.35	.44
FAGU073	12213	5.5	8.6	3.1	97	4A4	3.02	.03	3.80	7.40	52.0	.69	1.65	2.72		11.20	4.37	.66
FAGU073	12214	8.6	10.3	1.7	88	4D5	3.01	.05	4.30	5.20	52.0	.75	.93	3.06		9.50	3.99	.55
FAGU073	12215	10.3	12.0	1.7	100	4D5	2.92	.05	2.70	4.00	39.0	.89	1.12	2.41		6.70	3.53	.60
FAGU073	12216	12.0	13.4	1.4	100	4A0	2.89	.02	.38	.81	14.0	.41	1.05	4.36		1.19	5.41	.68
FAGU073	12217	13.4	15.4	2.0	100	4A3	3.44	.02	1.13	2.90	34.0	1.03	1.05	19.40		4.03	20.45	.72
FAGU073	12218	15.4	17.4	2.0	90	4A34	3.16	.02	2.60	5.00	51.0	.96	1.25	10.60		7.60	11.85	.66
FAGU073	12219	17.4	19.4	2.0	95	4A34	3.25	.03	2.90	8.60	52.0	1.17	1.51	9.90		11.50	11.41	.75
FAGU073	12220	19.4	21.4	2.0	90	4A34	3.36	.03	2.90	7.70	51.0	.96	1.10	13.10		10.60	14.20	.73
FAGU073	12221	21.4	23.2	1.8	94	4A34	3.17	.03	3.00	7.40	53.0	1.44	1.33	9.50		10.40	10.83	.71
FAGU073	12222	23.2	25.9	2.7	96	4E4	4.51	.15	5.60	11.80	113.0	1.51	.78	20.60		17.40	21.38	.68
FAGU073	12223	25.9	27.9	2.0	85	4G4	4.54	.14	7.30	11.80	131.0	2.40	2.11	27.40		19.10	29.51	.62
FAGU073	12224	27.9	29.8	1.9	100	4G4	4.67	.14	6.20	11.90	119.0	1.51	.83	21.20		18.10	22.03	.66
FAGU073	12225	29.8	31.6	1.8	100	4E4	4.15	.08	10.60	21.30	151.0	1.30	1.91	14.40		31.90	16.31	.67
FAGU073	12226	31.6	32.6	1.0	90	4E4	4.73	.15	8.50	15.40	153.0	.69	2.02	23.50		23.90	25.52	.64
FAGU073	12227	32.6	33.8	1.2	100	5D4*	3.28	.02	1.12	2.40	30.0	.41	2.05	10.00		3.52	12.05	.68
FAGU073	12228	33.8	35.4	1.6	19	4E4	4.45	.17	6.90	11.40	156.0	1.17	1.09	22.90		18.30	23.99	.62
FAGU109	12229	98.7	100.5	1.8	100	4A0	3.04	.06	1.14	2.70	21.0	.14	6.20	5.70		3.84	11.90	.70
FAGU107	12230	10.7	12.7	2.0	80	4A4	3.19	.03	1.67	3.40	37.0	.89	1.02	9.00		5.07	10.02	.67
FAGU107	12231	12.7	14.7	2.0	80	4A0	3.25	.05	1.42	2.80	33.0	1.03	2.81	9.20		4.22	12.01	.66
FAGU107	12232	14.7	16.7	2.0	65	4A0	3.36	.06	1.51	3.20	38.0	1.23	1.04	13.30		4.71	14.34	.68
FAGU107	12233	16.7	18.7	2.0	90	4A0	3.46	.08	.83	2.20	24.0	1.10	1.15	14.30		3.03	15.45	.73
FAGU107	12234	18.7	21.7	3.0	97	4A0	3.49	.06	1.42	2.20	33.0	1.23	.85	13.60		3.62	14.45	.61
FAGU107	12235	21.7	23.7	2.0	100	4A4	3.47	.05	2.80	4.20	50.0	1.51	1.12	12.80		7.00	13.92	.60
FAGU107	12236	23.7	25.7	2.0	100	4A4	3.52	.07	3.60	4.90	56.0	1.17	2.88	8.10		8.50	10.98	.58
FAGU107	12237	25.7	27.8	2.1	100	4A4	3.22	.05	2.70	5.20	52.0	1.10	.97	5.60		7.90	6.57	.66
FAGU107	12238	27.8	30.3	2.5	84	4A43	3.48	.05	5.70	11.80	101.0	1.37	1.52	8.40		17.50	9.92	.67
FAGU107	12239	30.3	32.8	2.5	100	4A43	3.57	.09	4.80	8.80	86.0	1.75	1.50	11.20		13.60	12.70	.65
FAGU107	12240	32.8	35.0	2.2	100	4D4	3.23	.06	3.20	8.10	58.0	.75	1.69	8.70		11.30	10.39	.72
FAGU107	12241	35.0	37.4	2.4	100	4D0	3.05	.04	3.00	5.20	52.0	1.71	1.49	3.84		8.20	5.33	.63
FAGU107	12242	37.4	38.6	1.2	100	5D4	3.27	.05	.51	.93	11.0	.89	6.62	7.50		1.44	14.12	.65
FAGU107	12243	42.0	42.6	.6	100	4D4	3.75	.09	7.70	15.30	144.0	.96	4.44	7.30		23.00	11.74	.67
FAGU107	12244	42.6	45.2	2.6	92	4A0	3.38	.14	.58	1.60	18.0	.96	1.83	12.80		2.18	14.63	.73
FAGU107	12245	45.2	47.7	2.5	100	4C5	3.05	.05	1.89	2.30	35.0	.62	1.01	4.12		4.19	5.13	.55
FAGU107	12246	47.7	50.2	2.5	100	4C5	2.94	.02	1.56	2.80	30.0	.41	1.01	1.10		4.36	2.11	.64
FAGU107	12247	50.2	52.2	2.0	85	4L14	3.20	.04	1.81	2.20	31.0	.55	1.67	3.66		4.01	5.33	.55

DDH	SAMPLE	---DEPTHS---	INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAO	PB+ZN	PO+PY	ZN
		FROM TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGU107	12248	57.4 60.7	3.3	100	4A03	3.54	.08	2.04	.34	43.0	1.03	1.15	16.50		2.38	17.65	.14
FAGU107	12249	60.7 62.5	1.8	89	4A43	3.38	.08	6.00	11.30	112.0	.69	2.13	8.90		17.30	11.03	.65
FAGA215	12251	61.7 63.7	2.0	45	4A0		.01	.04	.09	3.0					.13		.69
FAGA215	12252	63.7 65.7	2.0	75	4A0		.01	.01	.05	1.0					.06		.83
FAGA215	12253	65.7 67.0	1.3	100	4A0		.01	.20	.41	5.0					.61		.67
FAGA215	12254	67.0 69.0	2.0	85	4A0		.01	.06	.55	3.0					.61		.90
FAGA215	12255	69.0 71.0	2.0	90	4A0		.01	.01	.10	1.0					.11		.91
FAGA215	12256	71.0 72.4	1.4	100	4A0		.01	.01	.06	1.0					.07		.86
FAGA215	12257	72.4 73.8	1.4	79	4A0		.01	.52	.77	11.0					1.29		.60
FAGA215	12258	75.4 76.1	.7	86	4DC	3.21	.01	1.97	7.50	34.0	.27	5.90	5.90		9.47	11.80	.79
FAGA215	12259	76.1 77.0	.9	100	4C0	3.06	.01	1.88	3.40	29.0	.21	3.87	3.89		5.28	7.76	.64
FAGA215	12260	77.0 77.8	.8	100	4D0	3.15	.04	4.60	9.70	94.0	.41	6.61	6.30		14.30	12.91	.68
FAGA215	12261	77.8 78.3	.5	100	4E0	4.29	.04	2.31	9.60	57.0	.96	10.72	20.10		11.91	30.82	.81
FAGA215	12262	78.7 79.7	1.0	70	4E0	4.42	.08	1.94	3.30	39.0	.55	17.56	22.30		5.24	39.86	.63
FAGA215	12263	79.7 80.3	.6	100	4A0	3.46	.03	.94	3.40	23.0	.34	7.26	8.80		4.34	16.06	.78
FAGA215	12264	80.3 82.2	1.9	47	4D4	3.16	.02	2.40	6.10	42.0	.41	4.74	6.00		8.50	10.74	.72
FAGA215	12265	82.2 83.1	.9	78	4A4	3.57	.02	.84	5.40	20.0	.21	9.74	6.30		6.24	16.04	.87
FAGA215	12266	83.1 85.1	2.0	90	5A1		.01	.04	.33	5.0					.37		.89
FAGA215	12267	85.1 86.3	1.2	92	5A1		.01	.01	.20	6.0					.21		.95
FAGA215	12268	99.8 101.0	1.2	100	4A13	3.50	.08	4.00	6.50	64.0	1.10	1.78	12.30		10.50	14.08	.62
FAGA215	12269	101.5 102.4	.9	67	4L12	3.28	.05	.82	1.53	15.0	.48	3.94	10.90		2.35	14.84	.65
FAGA215	12270	102.8 103.3	.5	100	4D0	3.53	.03	3.50	6.90	47.0	.55	3.48	10.90		10.40	14.38	.66
FAGA215	12271	103.7 105.2	1.5	93	4A4	3.08	.01	2.50	5.40	36.0	.55	1.56	2.41		7.90	3.97	.68
FAGA215	12272	105.2 106.6	1.4	100	4A4	3.12	.02	2.32	4.20	40.0	.75	2.02	2.94		6.52	4.96	.64
FAGA215	12273	106.6 107.3	.7	86	4C0	4.14	.03	.74	3.30	15.0	.41	4.48	9.30		4.04	13.78	.82
FAGA215	12274	107.3 108.5	1.2	100	4A14	3.29	.04	1.93	3.70	35.0	.89	1.08	12.10		5.63	13.18	.66
FAGA215	12275	108.5 110.3	1.8	100	4L0	3.22	.02	.66	1.49	13.0	.34	3.52	3.12		2.15	6.64	.69
FAGA215	12276	110.3 111.8	1.5	100	4L0	3.18	.07	.95	1.42	18.0	.34	4.10	6.10		2.37	10.20	.60
FAGA215	12277	111.8 112.8	1.0	100	4L0	3.50	.04	1.18	1.51	23.0	.41	4.52	13.60		2.69	18.12	.56
FAGA215	12278	112.8 113.5	.7	100	4C3	3.66	.05	2.12	3.40	36.0	1.17	2.56	17.80		5.52	20.36	.62
FAGA215	12279	113.5 114.4	.9	89	4L3	3.10	.02	1.01	1.95	21.0	.55	4.02	6.50		2.96	10.52	.66
FAGA215	12280	114.4 115.8	1.4	93	5C4*	3.68	.05	10.80	16.90	155.0	.48	7.17	5.93		27.70	13.10	.61
FAGA215	12281	119.3 120.9	1.6	100	4L14	3.18	.04	1.62	3.00	30.0	.75	4.81	7.30		4.62	12.11	.65
FAGA215	12282	120.9 122.0	1.1	91	4L0	3.12	.07	.14	.82	10.0	.27	5.79	3.41		.96	9.20	.85
FAGA215	12283	122.0 123.0	1.0	90	4A14	3.21	.06	2.18	4.50	50.0	.62	4.67	6.80		6.68	11.47	.67
FAGA215	12284	123.0 123.3	.3	100	4D4	3.31	.06	2.92	7.50	46.0	.75	2.55	10.00		10.42	12.55	.72
FAGA215	12285	123.3 125.3	2.0	95	4A14	3.51	.07	6.61	12.70	106.0	1.30	1.94	7.50		19.31	9.44	.66
FAGA215	12286	127.3 129.1	1.8	100	4A14	3.27	.05	3.94	7.70	63.0	.96	1.34	9.70		11.64	11.04	.66
FAGA215	12287	129.1 131.1	2.0	95	4A13	3.12	.07	1.32	2.80	24.0	1.03	1.05	12.20		4.12	13.25	.68
FAGA215	12288	131.1 132.3	1.2	92	4A13	3.02	.03	1.92	2.70	36.0	.82	1.32	8.10		4.62	9.42	.58
FAGA215	12289	143.9 146.7	2.8	79	4A*		.01	.07	.14	4.0					.21		.67
FAGA215	12290	160.0 160.6	.6	100	4A0		.01	.01	.04	3.0					.05		.80
FAGA215	12291	160.6 161.8	1.2	92	5A19		.02	.64	2.20	15.0					2.84		.77
FAGA215	12292	161.8 162.4	.6	83	4D0		.02	1.55	4.70	27.0					6.25		.75
FAGA215	12293	210.8 212.1	1.3	92	4A0	2.86	.01	.01	.05	3.0	.14	2.27	1.67		.06	3.94	.83
FAGA215	12294	212.1 213.4	1.3	100	4A0	2.97	.02	.46	.73	10.0	.27	1.77	2.50		1.19	4.27	.61
FAGA215	12295	213.4 213.9	.5	100	4E4*	3.80	.13	6.60	9.90	133.0	1.44	3.16	16.50		16.50	19.66	.60
FAGA215	12296	213.9 214.7	.8	100	4E4*	4.60	.16	12.30	22.00	161.0	2.06	1.46	20.40		34.30	21.86	.64
FAGA215	12297	214.7 215.0	.3	100	4L*	3.96	.02	1.04	2.70	18.0	.48	2.88	6.90		3.74	9.78	.72
FAGA215	12298	215.0 215.4	.4	75	4K4	4.20	.06	4.90	11.70	90.0	1.37	2.08	23.00		16.60	25.08	.70

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAO	PB+ZN	PO+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGA215	12299	215.4	215.7	.3	100	4A0	3.98	.07	6.80	14.50	118.0	1.30	1.77	18.60		21.30	20.37	.68
FAGA215	12300	215.7	217.3	1.6	94	4G4*	4.48	.06	4.90	10.10	93.0	1.30	.87	15.50		15.00	16.37	.67
FAGA215	12301	217.3	219.3	2.0	70	4G4*	4.51	.08	4.10	8.00	70.0	1.17	.51	15.70		12.10	16.21	.66
FAGA215	12302	219.3	220.3	1.0	100	4G4*	4.58	.05	2.90	5.60	52.0	.96	1.00	13.40		8.50	14.40	.66
FAGA215	12303	220.3	222.5	2.2	95	4G4*	4.49	.08	5.70	10.10	104.0	1.37	.80	18.40		15.80	19.20	.64
FAGA215	12304	222.5	223.1	.6	100	4A14	3.23	.06	4.60	8.30	79.0	1.10	1.36	9.10		12.90	10.46	.64
FAGA215	12305	276.4	278.2	1.8	94	4E*	4.57	.16	6.00	5.70	80.0	.96	4.06	28.50		11.70	32.56	.49
FAGA215	12306	278.2	279.2	1.0		4L*3	3.11	.02	.97	1.06	19.0	.34	2.27	7.30		2.03	9.57	.52
FAGA215	12309	286.6	287.8	1.2	100	4E4	3.61	.08	3.30	3.50	44.0	1.58	3.53	16.70		6.80	20.23	.51
FAGA215	12310	287.8	288.6	.8	100	4E4*	3.37	.11	5.90	4.30	50.0	1.51	3.32	28.60		10.20	31.92	.42
FAGA215	12311	288.6	290.1	1.5	100	4E*		.19	.43	.71	14.0					1.14		.62
FAGA215	12312	290.1	291.6	1.5	100	4E8*	3.89	.18	.51	.46	16.0	1.51	5.71	23.10		.97	28.81	.47
FAGA215	12313	291.6	292.6	1.0	100	4E8*	4.20	.12	3.40	3.50	42.0	.89	7.26	26.70		6.90	33.96	.51
FAGA215	12314	292.6	293.8	1.2	100	4G48	3.18	.10	5.20	6.80	80.0	.82	5.30	14.00		12.00	19.30	.57
FAGA215	12315	293.8	294.5	.7	100	4G4	4.17	.15	5.90	8.20	95.0	1.65	2.24	16.10		14.10	18.34	.58
FAGA215	12316	294.5	294.8	.3	100	4D48	3.49	.15	2.60	3.20	35.0	.96	7.51	11.40		5.80	18.91	.55
FAGA215	12317	294.8	296.0	1.2	92	4E18	3.79	.31	1.52	2.40	33.0	.27	9.95	19.10		3.92	29.05	.61
FAGA215	12318	296.0	297.2	1.2	100	4E18	3.72	.24	.56	.69	18.0	.96	6.61	22.10		1.25	28.71	.55
FAGA215	12319	297.2	299.0	1.8	100	4C38	3.39	.19	.53	1.02	13.0	.89	7.91	14.50		1.55	22.41	.66
FAGA215	12320	299.0	300.9	1.9	95	4C38	3.53	.25	1.00	2.70	21.0	.96	5.42	16.70		3.70	22.12	.73
FAGA215	12321	300.9	301.6	.7	100	4D4	3.28	.23	.48	1.42	16.0	.89	3.83	14.00		1.90	17.83	.75
FAGA215	12322	301.6	303.3	1.7	100	4C38	3.36	.20	.70	2.60	17.0	.55	6.01	13.60		3.30	19.61	.79
FAGA215	12323	303.3	305.1	1.8	94	4C38	3.45	.37	.42	.83	14.0	.48	9.22	14.50		1.25	23.72	.66
FAGA215	12324	305.1	306.9	1.8	100	4C38	3.44	.26	.60	.71	13.0	.41	8.49	13.70		1.31	22.19	.54
FAGA215	12325	306.9	307.5	.6	100	4C8*	3.45	.16	.84	1.76	15.0	.48	9.46	13.50		2.60	22.96	.68
FAGA215	12326	307.5	309.2	1.7	94	4C37		.21	.43	.70	13.0					1.13		.62
FAGA215	12327	309.2	310.9	1.7	100	4C37		.27	.37	.70	12.0					1.07		.65
FAGA215	12328	310.9	312.6	1.7	100	4C37		.21	.19	.33	11.0					.52		.63
FAGA215	12329	313.5	314.8	1.3	100	4L*3		.49	.13	.38	13.0					.51		.75
FAGA215	12330	375.3	376.9	1.6	94	5A19		.01	.01	.01	6.0					.02		.50
FAGA216	12331	175.9	176.7	.8	87	4E18		.28	1.23	.99	27.0					2.22		.45
FAGA216	12332	176.7	177.9	1.2	92	4LE		.26	1.17	.68	22.0					1.85		.37
FAGA216	12333	188.3	189.6	1.3	92	4C7*		.07	.49	.51	15.0					1.00		.51
FAGA216	12334	190.7	191.3	.6	100	4C68	4.02	.30	1.16	.93	26.0	1.58	7.91	24.60		2.09	32.51	.44
FAGA216	12335	191.3	193.4	2.1	95	4C8*	3.90	.30	2.13	2.60	31.0	.82	11.10	18.40		4.73	29.50	.55
FAGA216	12336	193.4	194.7	1.3	92	4EG*	4.05	.36	3.30	3.10	46.0	.96	10.36	18.80		6.40	29.16	.48
FAGA216	12337	194.7	195.5	.8	100	4D8*	3.81	.23	2.50	2.90	37.0	.96	9.30	18.00		5.40	27.30	.54
FAGA216	12338	195.5	196.6	1.1	91	4E6*	3.62	.32	.88	.70	22.0	.82	7.77	17.80		1.58	25.57	.44
FAGA216	12339	196.6	197.3	.7	100	5A19	2.92	.08	.21	.14	10.0	.41	1.39	2.45		.35	3.84	.40
FAGA216	12340	197.3	199.4	2.1	95	4E1*	3.00	.25	1.44	1.41	29.0	.75	10.26	20.10		2.85	30.36	.49
FAGA216	12341	199.4	201.5	2.1	95	4E1*	3.65	.22	1.11	1.10	19.0	.89	8.32	16.60		2.21	24.92	.50
FAGA216	12342	201.5	204.0	2.5	92	4E1*	3.94	.19	2.80	2.40	34.0	.69	8.65	17.80		5.20	26.45	.46
FAGA216	12343	204.0	205.7	1.7	94	4EL	3.45	.14	1.21	.71	20.0	.75	4.09	14.70		1.92	18.79	.37
FAGA216	12344	205.7	207.4	1.7	94	4A1	3.19	.17	.21	.26	8.0	.96	2.91	12.90		.47	15.81	.55
FAGA216	12345	207.4	208.4	1.0	90	4E6*	3.94	.18	1.45	1.45	25.0	.96	6.12	23.30		2.90	29.42	.50
FAGA216	12346	208.4	208.8	.4	100	4L48	3.38	.17	1.96	1.71	28.0	.89	5.79	11.10		3.67	16.89	.47
FAGA216	12347	208.8	209.5	.7	86	4E16	3.82	.17	3.30	3.20	43.0	.89	7.55	18.40		6.50	25.95	.49
FAGA216	12348	209.5	211.4	1.9	95	4E8*	3.85	.34	1.47	1.20	25.0	.82	8.40	22.50		2.67	30.90	.45
FAGA216	12349	211.4	212.1	.7	100	4C78	3.90	.35	.80	.56	18.0	.89	13.05	20.60		1.36	33.65	.41
FAGA216	12350	215.3	215.8	.5	100	4G8#	3.86	.25	1.10	.80	19.0	.41	10.10	22.90		1.90	33.00	.42

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAG	PB+ZN	PO+PY	ZN
		FROM	TO	M.	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGA216	12351	216.4	217.7	1.3	92	4E16		.21	.96	.58	18.0					1.54		.38
FAGA216	12352	219.0	220.3	1.3	92	4G+8		.34	.80	.52	15.0					1.32		.39
FAGA216	12353	220.3	221.7	1.4	100	4G+8		.24	.92	.38	16.0					1.30		.29
FAGA216	12354	222.2	224.1	1.9	95	4E16		.21	1.24	1.17	21.0					2.41		.49
FAGA216	12355	224.1	224.6	.5	80	4L4		.14	.33	.36	10.0					.69		.52
FAGA216	12356	224.6	225.1	.5	100	4EL		.22	.26	.33	7.0					.59		.56
FAGA216	12357	225.1	226.6	1.5	93	4A13	4.53	.25	2.01	1.75	36.0	.55	8.10	20.10		3.76	28.20	.47
FAGA216	12358	226.6	228.1	1.5	93	4A13	4.53	.25	2.01	1.75	36.0	.55	8.10	20.10		3.76	28.20	.47
FAGA216	12359	228.1	228.6	.5	80	4G48	3.66	.26	2.80	4.10	45.0	.62	3.97	11.80		6.90	15.77	.59
FAGA216	12360	235.8	236.6	.8	100	4C0	3.35	.21	1.08	1.17	19.0	.41	4.86	12.00		2.25	16.86	.52
FAGA216	12361	237.1	237.7	.6	100	4G4	4.18	.13	6.50	6.40	94.0	.96	2.80	16.70		12.90	19.50	.50
FAGA216	12362	237.7	239.7	2.0	95	4A1	3.28	.24	.31	.27	9.0	.69	1.81	16.10		.58	17.91	.47
FAGA216	12363	239.7	240.6	.9	89	4A1	3.23	.16	1.21	1.13	17.0	.48	4.29	11.50		2.34	15.79	.48
FAGA216	12364	240.6	241.9	1.3	100	4A1	3.25	.19	.16	.22	7.0	.69	2.65	13.80		.38	16.45	.58
FAGA216	12365	241.9	243.0	1.1	91	4A1	3.37	.14	2.13	2.80	33.0	.75	1.93	15.30		4.93	17.23	.57
FAGA216	12366	243.0	243.8	.8	88	4E1	4.14	.14	.36	.26	14.0	1.17	3.60	29.90		.62	33.50	.42
FAGA216	12367	243.8	244.3	.5	80	4C3	3.61	.22	1.55	.41	32.0	.89	2.98	17.20		1.96	20.18	.21
FAGA216	12368	244.3	246.3	2.0	95	4C83	3.43	.20	1.18	.87	22.0	.55	6.52	12.40		2.05	18.92	.42
FAGA216	12369	246.3	247.4	1.1	91	4E16	3.65	.22	.76	.73	18.0	.82	8.68	16.90		1.49	25.58	.49
FAGA216	12370	247.4	249.3	1.9	95	4E1	3.11	.13	.58	.61	12.0	.21	5.18	9.10		1.19	14.28	.51
FAGA216	12371	261.5	262.9	1.4	100	5A19		.01	.02	.03	4.0					.05		.60
FAGA216	12372	262.9	264.3	1.4	93	5A19		.01	.01	.03	4.0					.04		.75
FAGA216	12373	265.3	266.8	1.5	93	5A19		.01	.01	.01	5.0					.02		.50
FAGA216	12374	266.8	268.2	1.4	100	5A19		.01	.01	.02	4.0					.03		.67
FAGA216	12375	362.2	364.4	2.2	95	4L4		.03	.19	.40	5.0					.59		.68
FAGA216	12376	364.4	366.6	2.2	95	4L4		.01	.01	.03	4.0					.04		.75
FAGA215	12377	125.3	127.3	2.0	95	4A14			4.50	8.70	68.0					13.20		.66
FAGA119	12401	49.0	50.2	1.2	92	4GE		.03	2.34	6.50	44.0					8.84		.74
FAGA119	12402	50.2	51.5	1.3	100	4GE		.01	2.25	6.30	43.0					8.55		.74
FAGA119	12403	51.5	52.8	1.3	92	4GE		.01	2.09	5.70	37.0					7.79		.73
FAGA119	12404	115.2	116.1	.9	67	4E0		.29	1.25	1.64	25.0					2.89		.57
FAGAG08	12405	98.1	99.4	1.3	38	4A0		.03	1.71	2.88	22.0					4.59		.63
FAGA008	12406	99.4	100.8	1.4	57	4A0		.03	1.49	2.02	20.0					3.51		.58
FAGA225	12407	155.0	156.4	1.4	100	4E41		.17	6.23	8.26	67.0					14.49		.57
FAGA225	12408	58.2	59.5	1.3	85	4A0		.03	2.11	2.70	36.0					4.81		.56
FAGA225	12409	59.5	60.8	1.3	100	4A0		.02	.08	.23	3.0					.31		.74
FAGA225	12410	60.8	62.0	1.2	83	4A0		.02	.27	.53	5.0					.80		.66
FAGA225	12411	69.0	69.6	.6	83	4LE	3.55	.01	.12	3.23	4.0	.34	2.50	12.10		3.35	14.60	.96
FAGA225	12412	69.6	70.7	1.1	82	4E4	4.82	.28	12.50	20.50	184.0	2.13	.85	21.80		33.00	22.65	.62
FAGA225	12413	70.7	72.0	1.3	69	4G4	4.89	.22	7.11	10.90	148.0	1.37	1.66	23.30		18.01	24.96	.61
FAGA225	12414	72.0	73.3	1.3	85	4G4	4.81	.18	6.03	9.00	114.0	1.65	.69	19.50		15.03	20.19	.60
FAGA225	12415	73.3	74.0	.7	86	4E4	4.92	.17	4.67	9.10	73.0	2.19	21.70	1.93		13.77	23.63	.66
FAGA225	12416	74.5	75.0	.5	100	4CG		.09	1.05	1.62	16.0					2.67		.61
FAGA225	12417	93.3	94.5	1.2	92	4A0		.03	.34	.62	7.0					.96		.65
FAGA225	12419	96.1	96.7	.6	100	4A0		.04	.02	.06	4.0					.08		.75
FAGA225	12420	103.6	104.2	.6	100	4A1		.06	.04	.07	4.0					.11		.64
FAGA225	12421	104.6	105.1	.5	100	4A1		.06	.13	.56	6.0					.69		.81
FAGA225	12422	105.1	106.6	1.5	93	4L1		.03	.03	.07	4.0					.10		.70
FAGA225	12423	107.5	108.1	.6	100	4LC		.09	.19	.67	7.0					.86		.78
FAGA225	12424	133.5	133.8	.3	100	4H14		.06	3.28	11.10	56.0					14.38		.77

DDH	SAMPLE	----DEPTHS----		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAG	PB+ZN	PC+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGA225	12425	141.3	142.7	1.4	100	4D7		.20	2.88	5.00	38.0					7.88		.63
FAGA227	12426	57.9	60.4	2.5	92	4A4	2.96	.06	1.79	3.47	38.0	.62	1.08	5.60		5.26	6.68	.66
FAGA227	12427	60.4	62.9	2.5	100	4A0	2.92	.04	1.17	1.83	24.0	.27	.66	5.30		3.00	5.96	.61
FAGA227	12428	62.9	64.1	1.2	100	4C5	2.80	.02	1.24	3.09	24.0	.14	1.28	1.17		4.33	2.45	.71
FAGA227	12429	64.1	65.5	1.4	100	4D54	3.10	.04	4.67	8.77	82.0	.82	1.54	5.60		13.44	7.14	.65
FAGA227	12430	65.5	66.9	1.4	100	4D54	3.20	.08	6.35	11.00	103.0	.89	2.18	4.12		17.35	6.30	.63
FAGA227	12431	66.9	70.0	3.1	100	4A0	2.92	.08	1.15	2.00	22.0	.34	1.08	4.10		3.15	5.18	.63
FAGA227	12433	70.0	71.4	1.4	100	4A0		.08	.94	.19	18.0					1.13		.17
FAGA227	12434	71.4	73.3	1.9	100	5A19		.02	.22	.47	6.0					.69		.68
FAGA227	12435	73.3	75.6	2.3	100	4A4	3.31	.04	3.64	6.62	72.0	.48	2.00	9.70		10.26	11.70	.65
FAGA227	12436	75.6	77.6	2.0	100	4E4	4.31	.08	8.82	18.70	188.0	1.37	3.65	15.40		27.52	19.05	.68
FAGA227	12437	131.4	132.1	.7	100	4A4		.04	4.48	11.70	82.0					16.18		.72
FAGA227	12438	134.7	137.1	2.4		4A0		.04	1.26	1.80	22.0					3.06		.59
FAGA228	12439	52.8	54.8	2.0	95	4D5	2.86	.02	2.03	5.77	40.0	.21	1.25	.52		7.80	1.77	.74
FAGA228	12440	54.8	56.0	1.2	83	4D5	2.88	.04	1.82	6.55	46.0	.21	1.40	.58		8.37	1.98	.78
FAGA228	12441	56.0	58.0	2.0	95	4D0	2.88	.02	2.08	5.77	41.0	.27	1.29	.68		7.85	1.97	.73
FAGA228	12442	58.0	60.1	2.1	100	4D0	2.92	.05	3.24	6.48	46.0	.41	1.22	1.31		9.72	2.53	.67
FAGA228	12443	60.1	61.0	.9	100	4D0	2.99	.08	3.52	2.41	45.0	.75	1.13	5.42		5.93	6.55	.41
FAGA228	12444	61.0	63.0	2.0	70	4D0	2.93	.04	2.96	3.17	38.0	.89	.91	2.84		6.13	3.75	.52
FAGA228	12445	63.0	65.3	2.3	78	4D0	2.92	.05	2.65	5.36	40.0	.41	1.19	2.93		8.01	4.12	.67
FAGA228	12446	65.3	67.9	2.6	77	4C5	2.93	.07	1.42	3.24	24.0	.48	1.40	4.24		4.66	5.64	.70
FAGA228	12447	67.9	69.9	2.0	75	4CA	2.84	.05	1.11	2.65	20.0	.48	.85	2.60		3.76	3.45	.70
FAGA228	12448	69.9	71.1	1.2	58	4CA	2.88	.04	.88	2.64	17.0	.41	.88	3.92		3.52	4.80	.75
FAGA228	12449	71.1	72.8	1.7	94	4C5	2.87	.05	1.21	2.51	18.0	.48	1.01	3.96		3.72	4.97	.67
FAGA228	12450	85.2	87.2	2.0	100	4A0		.02	.37	.73	9.0					1.10		.66
FAGA228	12451	87.2	88.7	1.5	93	4A1	3.13	.02	1.58	2.76	33.0	.41	2.45	7.90		4.34	10.35	.64
FAGA228	12452	88.7	90.5	1.8	100	4A41	3.20	.03	3.86	6.60	86.0	.55	2.18	7.80		10.46	9.98	.63
FAGA228	12453	90.5	91.3	.8	87	4A0	3.29	.02	1.89	2.15	35.0	.01	1.78	11.70		4.04	13.48	.53
FAGA228	12454	91.3	93.5	2.2	91	4A14	3.26	.02	2.76	4.26	59.0	.21	2.34	8.10		7.02	10.44	.61
FAGA228	12455	95.8	97.2	1.4	100	4JD7	4.02	.06	12.90	22.70	369.0	1.23	12.40	3.70		35.60	16.10	.64
FAGA228	12456	118.0	119.0	1.0	90	4G4	4.23	.10	6.34	9.12	117.0	1.37	3.93	23.00		15.46	26.93	.59
FAGA228	12457	121.5	122.0	.5	100	4D4		.06	7.36	7.26	105.0					14.62		.50
FAGA228	12458	125.3	126.5	1.2	100	4A4	3.30	.04	4.69	10.30	78.0	.89	2.01	8.40		14.99	10.41	.69
FAGA228	12459	128.1	130.5	2.4	96	4A4	3.31	.03	2.79	6.63	54.0	.75	2.98	7.40		9.42	10.38	.70
FAGA228	12460	132.3	133.6	1.3	100	4D0	3.34	.03	3.16	6.79	67.0	.41	3.90	8.90		9.95	12.80	.68
FAGA228	12461	133.6	135.7	2.1	100	4A4	3.28	.03	2.14	5.13	42.0	.55	2.39	11.10		7.27	13.49	.71
FAGA228	12462	135.7	137.7	2.0	100	4A4	3.63	.03	3.83	8.50	86.0	1.10	1.91	16.50		12.33	18.41	.69
FAGA228	12463	137.7	139.2	1.5	100	4A0	3.46	.02	1.45	3.32	32.0	.01	2.30	17.10		4.77	19.40	.70
FAGA228	12464	139.2	141.0	1.8	94	4A4	3.26	.03	2.45	4.99	42.0	.55	.97	11.00		7.44	11.97	.67
FAGA228	12465	143.6	145.8	2.2	91	4AE	3.09	.03	1.74	4.19	29.0	.48	3.55	4.24		5.93	7.79	.71
FAGA229	12466	103.0	104.8	1.8		4A4	2.95	.01	1.39	5.40	29.0	.14	1.89	3.17		6.79	5.06	.80
FAGA229	12467	104.8	105.5	.7		4C0	2.99	.01	.73	2.73	15.0	.14	3.71	.61		3.46	4.32	.79
FAGA229	12468	105.5	107.3	1.8		4A0	2.90	.02	.88	2.34	18.0	.01	2.02	1.06		3.22	3.08	.73
FAGA229	12469	107.3	108.8	1.5		4A0	2.87	.02	.83	1.55	14.0	.07	1.16	1.37		2.38	2.53	.65
FAGA230	12470	83.7	85.4	1.7	94	4EDH	4.25	.02	.78	2.92	21.0	.62	4.05	30.10		3.70	34.15	.79
FAGA230	12471	85.7	87.5	1.8	89	4EDH	4.18	.02	2.50	10.20	30.0	.55	5.10	23.40		12.70	28.50	.80
FAGA230	12472	90.4	92.5	2.1	95	4A4	3.04	.02	2.61	6.30	42.0	.27	2.12	3.33		8.91	5.45	.71
FAGA230	12473	92.5	94.3	1.8	100	4A4	3.02	.05	3.47	6.50	58.0	.27	2.06	2.57		9.97	4.63	.65
FAGA230	12474	102.7	103.3	.6	83	4A4	3.04	.12	2.22	5.50	43.0	.55	1.85	3.49		7.72	5.34	.71
FAGA230	12475	103.3	105.7	2.4	96	4D0	3.16	.03	1.47	3.82	28.0	.14	4.06	4.34		5.29	8.40	.72

DDH	SAMPLE	---DEPTHS---	INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAO	PB+ZN	PC+PY	ZN
		FROM TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGA230	12476	105.7 107.7	2.0	95	4A4	3.06	.04	2.61	5.28	48.0	.34	1.34	4.41		7.89	5.75	.67
FAGA230	12477	107.7 109.7	2.0	100	4A4	3.02	.03	2.25	3.85	35.0	.34	1.23	2.70		6.10	3.93	.63
FAGA230	12478	109.7 111.5	1.8	83	4A4	3.23	.02	1.58	4.68	25.0	.34	1.30	7.60		6.26	8.90	.75
FAGA230	12479	114.1 115.8	1.7	100	4A0		.02	.41	2.03	10.0					2.44		.83
FAGA230	12480	117.9 119.8	1.9	95	4A4	3.16	.03	4.62	6.17	70.0	.55	1.18	5.20		10.79	6.38	.57
FAGA230	12481	119.8 121.6	1.8	94	4A4	3.12	.04	3.22	5.98	48.0	.41	1.74	5.10		9.20	6.84	.65
FAGA230	12482	136.8 138.1	1.3	85	4A4	3.56	.03	2.33	4.89	29.0	.21	3.95	14.40		7.22	18.35	.68
FAGA230	12483	139.6 142.4	2.8	93	4A4	3.13	.03	3.67	7.80	64.0	.41	2.58	5.72		11.47	8.30	.68
FAGA230	12484	143.0 144.2	1.2	83	4DA	3.01	.01	1.55	5.29	25.0	.14	2.42	4.30		6.84	6.72	.77
FAGA230	12485	147.8 149.2	1.4	100	4A4	3.50	.03	3.83	9.84	83.0	.07	4.79	9.60		13.67	14.39	.72
FAGA230	12486	150.2 151.0	.8	88	4AD	3.02	.01	2.06	6.01	44.0	.14	4.00	2.35		8.07	6.35	.74
FAGA230	12487	153.0 155.1	2.1	67	4A4	3.35	.01	4.76	11.30	90.0	.21	2.50	7.00		16.06	9.50	.70
FAGA230	12488	162.0 165.1	3.1	87	4A4	3.03	.01	1.39	4.21	28.0	.21	1.29	6.30		5.60	7.59	.75
FAGA230	12489	165.6 167.9	2.3	87	4A0	2.92	.03	1.03	2.16	17.0	.14	3.77	1.33		3.19	5.10	.68
FAGA224	12490	124.9 125.8	.9	100	4A1		.06	.26	.50	8.0					.76		.66
FAGA224	12491	125.8 126.7	.9	100	4E0*		.16	.92	.96	22.0					1.88		.51
FAGA224	12492	137.8 138.6	.8	87	4A0		.19	.45	.32	11.0					.77		.42
FAGA218	12493	98.4 99.8	1.4	50	4A1		.02	.04	.07	2.0					.11		.64
FAGA218	12494	99.8 101.2	1.4	100	4A1		.03	.04	.10	2.0					.14		.71
FAGA218	12495	106.2 106.8	.6	100	4L0		.05	1.01	.77	19.0					1.78		.43
FAGA218	12496	106.8 109.0	2.2	100	4H64		.16	7.55	8.86	102.0					16.41		.54
FAGA218	12497	109.5 109.9	.4	100	4A4@		.21	2.56	2.45	38.0					5.01		.49
FAGA225	12498	142.7 144.1	1.4	100	4C7	4.16					.34	12.30	8.00			20.30	
FAGA225	12499	144.1 145.4	1.3	100	4C7		.22	.42	.32	10.0					.74		.43
FAGA225	12500	146.0 147.7	1.7	100	4D7	4.17	.23	2.80	2.54	38.0	.27	13.80	11.20		5.34	25.00	.48
FAGA087	12501	171.0 172.2	1.2	75	4A0	3.14	.03	1.54	3.07	27.0	.48	1.21	10.30		4.61	11.51	.67
FAGA087	12502	172.2 173.7	1.5	93	4A0	2.90	.06	1.04	1.22	17.0	.34	.94	3.61		2.26	4.55	.54
FAGA087	12503	173.7 175.3	1.6	100	4A0		.08	.45	.80	10.0					1.25		.64
FAGA087	12504	175.3 176.3	1.0	100	4A0		.12	.60	1.06	12.0					1.66		.64
FAGA087	12505	183.0 184.0	1.0	100	4C5	3.47	.08	1.28	1.95	22.0	.41	2.26	17.20		3.23	19.46	.60
FAGA087	12506	184.0 185.7	1.7	100	4A0	3.20	.05	1.41	2.05	26.0	.34	2.84	10.60		3.46	13.44	.59
FAGA087	12507	189.3 191.1	1.8	100	4C5	3.08	.08	1.81	2.57	28.0	.55	2.52	6.00		4.38	8.52	.59
FAGA087	12508	191.1 192.8	1.7	94	4C5	2.91	.05	1.58	1.58	21.0	.41	1.57	4.26		3.16	5.83	.50
FAGA087	12509	192.8 194.4	1.6	100	4C5	3.02	.09	1.32	1.66	25.0	.69	1.01	7.00		2.98	8.01	.56
FAGA087	12510	194.4 196.0	1.6	100	4C5	2.89	.04	1.22	.93	19.0	.07	.87	3.30		2.15	4.17	.43
FAGA087	12511	196.0 197.7	1.7	94	4C5		.02	.88	.63	12.0					1.51		.42
FAGA087	12512	197.7 199.2	1.5	100	4C5		.03	.96	.87	14.0					1.83		.48
FAGA087	12513	206.0 207.6	1.6	94	4C0	2.86	.03	1.07	1.86	17.0	.34	1.02	.80		2.93	1.82	.63
FAGA087	12514	207.6 209.1	1.5	100	4C0	2.91	.04	1.50	3.30	28.0	.34	1.37	.99		4.80	2.36	.69
FAGA087	12515	209.1 210.6	1.5	100	4C0	2.87	.02	1.17	2.28	22.0	.69	1.00	.48		3.45	1.48	.66
FAGA087	12516	210.6 212.1	1.5	100	4C0	2.92	.04	1.32	2.34	23.0	.34	1.27	2.25		3.66	3.52	.64
FAGA087	12517	212.1 213.7	1.6	94	4C0	2.88	.04	1.33	2.82	23.0	.27	1.32	1.13		4.15	2.45	.68
FAGA087	12518	213.7 215.2	1.5	100	4C0	2.87	.03	1.24	2.87	21.0	.69	.95	1.32		4.11	2.27	.70
FAGA087	12519	215.2 216.7	1.5	100	4C0	2.96	.03	1.52	3.44	29.0	.82	.90	3.78		4.96	4.68	.69
FAGA087	12520	216.7 218.2	1.5	100	4C0	3.04	.03	1.08	1.83	21.0	.62	1.99	4.70		2.91	6.69	.63
FAGA087	12521	218.2 219.9	1.7	94	4C0	2.99	.03	1.39	3.06	28.0	.62	1.15	5.30		4.45	6.45	.69
FAGA087	12522	239.3 240.4	1.1	100	4A1		.07	.38	1.77	15.0					2.15		.82
FAGA087	12523	249.2 250.5	1.3	100	4A4	3.09	.06	3.82	4.28	68.0	1.17	1.39	6.60		8.10	7.99	.53
FAGA087	12524	313.6 315.0	1.4	93	4A0	3.15	.07	1.29	2.03	21.0	.69	1.43	10.60		3.32	12.03	.61
FAGA087	12525	315.0 315.5	.5	100	4G4	4.46	.06	6.00	11.10	100.0	1.30	1.06	20.10		17.10	21.16	.65

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAC	PB+ZN	PO+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGA087	12526	315.5	317.6	2.1	100	4A0		.16	.66	.82	14.0					1.48		.55
FAGA087	12527	347.7	349.4	1.7	94	4A0	3.48	.14	1.20	2.00	33.0	.41	3.68	17.50		3.20	21.18	.63
FAGA087	12528	349.4	350.2	.8	100	4C3	3.56	.53	1.73	2.87	47.0	.48	6.30	16.40		4.60	22.70	.62
FAGA087	12529	351.2	351.7	.5	100	4E4		.18	3.09	2.72	44.0					5.81		.47
FAGA087	12530	394.4	395.5	1.1	100	4H4	3.57	.16	6.10	8.90	55.0	.27	11.00	7.10		15.00	18.10	.59
FAGA093	12531	76.5	77.1	.6		4D0	3.09	.04	2.12	4.64	33.0	.41	2.83	6.70		6.76	9.53	.69
FAGA093	12532	77.1	78.5	1.4		4A4	3.06	.03	2.51	5.50	48.0	.41	3.04	4.81		8.01	7.85	.69
FAGA093	12533	79.1	80.5	1.4		4A4	2.96	.04	2.75	6.00	48.0	.62	1.82	2.93		8.75	4.75	.69
FAGA093	12534	80.5	81.9	1.4		4A4	3.20	.12	2.76	4.26	47.0	1.44	2.51	9.10		7.02	11.61	.61
FAGA093	12535	106.6	108.7	2.1		4C5	2.91	.05	.85	1.88	16.0	.41	1.37	4.31		2.73	5.68	.69
FAGA093	12536	108.7	110.8	2.1		4C5	2.99	.10	1.12	2.58	23.0	.69	1.13	6.40		3.70	7.53	.70
FAGA093	12537	110.8	112.8	2.0		4C5	2.91	.08	1.41	2.81	25.0	.48	1.33	2.67		4.22	4.00	.67
FAGA093	12538	137.0	137.5	.5		4E4		.05	7.50	14.80	170.0					22.30		.66
FAGA093	12539	139.2	140.5	1.3		4A41	3.36	.09	5.50	8.80	90.0	1.30	2.97	8.80		14.30	11.77	.62
FAGA093	12540	142.0	143.6	1.6		4EL		.04	2.15	2.26	37.0					4.41		.51
FAGA093	12543	298.4	300.1	1.7		4C5	2.92	.03	1.71	2.43	27.0	.62	1.36	3.33		4.14	4.69	.59
FAGA093	12544	300.1	301.9	1.8		4C5	2.91	.03	1.32	2.69	22.0	.62	1.62	2.92		4.01	4.54	.67
FAGA093	12545	302.1	302.7	.6		4E46	3.97	.06	3.54	5.90	57.0	.69	1.46	15.20		9.44	16.66	.63
FAGA093	12546	303.5	304.9	1.4		4C5		.03	1.03	1.55	18.0					2.58		.60
FAGA093	12547	348.0	348.5	.5		4AH4		.08	2.84	4.77	48.0					7.61		.63
FAGA089	12548	94.9	97.1	2.2	68	4A4	3.28	.02	1.98	4.67	35.0	.55	1.60	12.50		6.65	14.10	.70
FAGA089	12549	97.1	99.3	2.2	86	4A4	3.21	.04	2.71	3.06	44.0	1.10	1.50	11.10		5.77	12.60	.53
FAGA089	12550	99.3	100.8	1.5	93	4D0	3.04	.05	1.64	3.19	32.0	.48	2.65	7.10		4.83	9.75	.66
FAGA089	12551	100.8	102.3	1.5	100	4D0	3.03	.03	1.68	3.38	28.0	.96	3.42	5.60		5.06	9.02	.67
FAGA089	12552	143.0	144.2	1.2	92	4E41	4.10	.17	2.86	4.25	61.0	1.51	3.95	27.60		7.11	31.55	.60
FAGA089	12553	144.2	146.5	2.3	96	4A34	3.56	.10	3.92	3.79	52.0	1.58	1.77	16.60		7.71	18.37	.49
FAGA089	12554	146.5	148.8	2.3	96	4A34	3.35	.06	3.80	6.00	55.0	1.30	1.80	12.70		9.80	14.50	.61
FAGA089	12555	148.8	151.1	2.3	96	4A3		.04	.44	1.18	10.0					1.62		.73
FAGA089	12556	151.1	153.7	2.6	100	4L74	2.93	.02	1.59	2.53	26.0	.41	1.81	1.97		4.12	3.78	.61
FAGA089	12557	153.7	154.9	1.2		4C5	3.16	.03	1.33	1.62	20.0	.55	1.75	10.60		2.95	12.35	.55
FAGA089	12558	156.9	158.2	1.3		4A4		.05	2.97	5.30	47.0					8.27		.64
FAGA089	12559	162.2	163.7	1.5		4EL4	3.92	.19	3.49	7.40	66.0	1.37	2.90	20.80		10.89	23.70	.68
FAGA089	12560	178.7	180.3	1.6		4A41	3.39	.04	3.61	6.60	86.0	1.10	2.13	11.70		10.21	13.83	.65
FAGA089	12561	180.6	182.1	1.5		4A4	3.18	.08	2.64	3.99	34.0	1.58	5.50	5.40		6.63	10.90	.60
FAGA089	12562	269.7	272.3	2.6		4D54	3.45	.09	5.70	9.00	95.0	.69	1.93	8.00		14.70	9.93	.61
FAGA089	12563	280.8	281.6	.8		4D5	3.35	.03	2.69	7.10	50.0	.62	1.97	8.40		9.79	10.37	.73
FAGA089	12564	281.9	282.8	.9		4D5	3.38	.02	3.50	7.60	67.0	.96	1.64	8.80		11.10	10.44	.68
FAGA089	12565	283.3	285.3	2.0		4D5	3.14	.01	2.66	6.90	46.0	.48	1.85	5.30		9.56	7.15	.72
FAGA089	12566	285.3	287.2	1.9		4D5	2.96	.01	.96	3.40	19.0	.34	2.34	3.52		4.36	5.86	.78
FAGA089	12567	287.2	290.0	2.8		4D5	3.15	.05	3.60	4.08	50.0	1.10	1.28	8.40		7.68	9.68	.53
FAGA089	12568	290.0	291.8	1.8		4D5	3.07	.05	2.64	2.56	36.0	1.37	1.73	7.80		5.20	9.53	.49
FAGA089	12569	293.4	294.8	1.4		4DC57		.05	1.40	1.17	21.0					2.57		.46
FAGA089	12570	296.3	297.3	1.0		4DEG	3.99	.08	6.30	8.90	100.0	1.23	2.00	19.40		15.20	21.40	.59
FAGA089	12571	358.0	358.7	.7		4E46	4.26	.21	3.87	4.87	66.0	1.92	2.00	29.40		8.74	31.40	.56
FAGA089	12572	358.7	359.9	1.2		4D35	3.67	.01	2.65	4.50	46.0	.82	1.63	19.60		7.15	21.23	.63
FAGA089	12573	359.9	361.2	1.3		4E4	4.03	.15	3.00	3.56	54.0	.89	2.28	24.00		6.56	26.28	.54
FAGA089	12574	369.4	370.4	1.0		4EAG	3.62	.03	3.45	3.79	43.0	.82	2.85	13.80		7.24	16.65	.52
FAGA089	12575	371.0	372.5	1.5		4E4	4.51	.14	3.76	3.09	40.0	1.51	6.35	25.50		6.85	31.85	.45
FAGA089	12576	372.5	374.0	1.5		4E4	4.50	.17	4.40	3.93	42.0	1.23	7.32	23.20		8.33	30.52	.47
FAGA089	12577	374.0	375.6	1.6		4CG	3.95	.22	2.64	2.08	31.0	1.37	5.08	21.70		4.72	26.78	.44

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAO	PB+ZN	PC+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGA089	12578	375.6	377.2	1.6		4CG	3.79	.29	1.81	1.64	27.0	.89	4.46	22.00		3.45	26.46	.48
FAGA085	12579	181.4	184.7	3.3		4A4	3.27	.04	2.42	4.86	43.0	.48	2.47	10.90		7.28	13.37	.67
FAGA085	12580	184.7	185.9	1.2		4C0	3.07	.07	.81	1.66	16.0	.34	2.94	10.40		2.47	13.34	.67
FAGA085	12581	185.9	187.3	1.4		4A4	3.14	.05	1.85	3.80	33.0	.69	3.97	5.10		5.65	9.07	.67
FAGAG85	12582	187.3	189.3	2.0		4A0	2.98	.05	.78	1.64	15.0	.55	1.15	5.60		2.42	6.75	.68
FAGA085	12583	189.3	191.1	1.8		4A0	2.89	.06	1.32	2.62	24.0	.48	1.20	2.60		3.94	3.80	.66
FAGA085	12584	191.1	192.9	1.8		4A0	2.87	.03	1.34	1.60	23.0	.69	.95	2.63		2.94	3.58	.54
FAGA085	12585	192.9	195.1	2.2		4A0	2.93	.03	1.33	1.60	24.0	.62	1.36	4.13		2.93	5.49	.55
FAGA085	12586	195.1	196.9	1.8		4A0		.11	.52	.65	13.0					1.17		.56
FAGAG85	12587	224.5	225.4	.9		4C5	2.84	.03	1.07	1.83	17.0	.27	2.05	.89		2.90	2.94	.63
FAGA085	12588	225.4	228.1	2.7		4C5	2.88	.09	1.73	2.32	29.0	.62	2.59	2.80		4.05	5.39	.57
FAGA085	12589	228.1	230.4	2.3		4D5	2.99	.05	2.98	2.77	48.0	.75	1.76	1.96		5.75	3.72	.48
FAGA085	12590	230.4	232.3	1.9		4C5	2.93	.04	2.11	.55	28.0	.62	.91	2.16		2.66	3.07	.21
FAGA085	12591	232.3	234.1	1.8		4C5	2.89	.02	2.46	2.21	31.0	.69	1.28	1.04		4.67	2.32	.47
FAGAG85	12592	234.1	235.9	1.8		4C5	2.86	.01	1.31	3.27	21.0	.41	1.51	.35		4.58	1.86	.71
FAGA085	12593	235.9	237.7	1.8		4C5	2.97	.02	1.00	1.59	14.0	.34	1.67	1.29		2.59	2.96	.61
FAGA085	12594	237.7	239.6	1.9		4C5	3.00	.05	1.45	1.60	23.0	.69	2.05	1.62		3.05	3.67	.52
FAGAG85	12595	242.8	244.6	1.8		4C5	2.98	.04	2.26	3.20	35.0	.82	1.46	2.02		5.46	3.48	.59
FAGAG85	12596	244.6	246.1	1.5		4C5	2.98	.08	1.32	2.70	26.0	.75	2.99	1.97		4.02	4.96	.67
FAGA085	12597	246.1	246.9	.8		4C0		.02	.63	1.63	9.0					2.26		.72
FAGA085	12598	288.6	290.8	2.2		4A0		.12	.88	1.15	22.0					2.03		.57
FAGA085	12599	290.8	292.9	2.1		4A0		.08	.77	1.06	15.0					1.83		.58
FAGA085	12600	296.0	299.3	3.3		4A0	3.12	.07	1.12	1.42	19.0	.69	1.68	11.10		2.54	12.78	.56
FAGA085	12601	302.8	304.2	1.4		4A0		.22	.13	.36	11.0					.49		.73
FAGA085	12602	304.2	306.3	2.1		4EG	4.56	.10	6.90	12.70	131.0	1.17	.96	19.20		19.60	20.16	.65
FAGAG85	12603	352.3	354.8	2.5		4E0	4.47	.33	2.56	3.00	43.0	1.78	1.90	33.50		5.56	35.40	.54
FAGAG85	12604	354.8	357.0	2.2		4E0	4.70	.36	2.53	2.74	55.0	1.85	2.15	37.60		5.27	39.75	.52
FAGA085	12605	357.8	359.4	1.6		4D45	3.56	.10	7.70	17.50	148.0	1.65	2.67	8.20		25.20	10.87	.69
FAGA085	12606	359.4	360.6	1.2		4D45	3.63	.11	8.00	12.40	150.0	1.99	3.30	10.00		20.40	13.30	.61
FAGAG85	12607	392.4	393.5	1.1		4C0	3.16	.10	1.25	1.27	20.0	.34	4.57	6.60		2.52	11.17	.50
FAGA231	12608	117.8	119.3	1.5	73	4A4	3.26	.03	3.12	7.88	56.0	.41	3.91	1.63		11.00	5.54	.72
FAGA231	12609	119.3	120.7	1.4	100	4A4	3.60	.03	5.13	11.85	116.0	.55	3.13	2.55		16.98	5.68	.70
FAGA231	12610	121.0	122.7	1.7	100	4A4	3.40	.03	3.60	8.48	81.0	.27	1.66	2.24		12.08	3.90	.70
FAGA231	12611	123.3	123.9	.6	100	4A4		.02	2.96	7.88	71.0					10.84		.73
FAGA231	12612	152.2	154.0	1.8	100	4A4	3.60	.02	2.85	9.62	59.0	.41	6.60	2.60		12.47	9.20	.77
FAGA231	12613	154.0	155.6	1.6	94	4A4	3.27	.02	3.04	6.59	60.0	.27	1.99	2.36		9.63	4.35	.68
FAGA231	12614	155.6	157.3	1.7	94	4A4	3.28	.02	2.08	6.65	46.0	.14	2.61	1.34		8.73	3.95	.76
FAGA231	12615	157.3	159.3	2.0		4A4	3.19	.02	1.56	5.66	38.0	.34	1.64	.96		7.22	2.60	.78
FAGA231	12616	159.3	161.1	1.8		4A4	3.18	.01	1.59	6.29	39.0	.27	2.21	1.12		7.88	3.33	.80
FAGA231	12617	164.2	165.4	1.2		4A0	3.39	.01	.82	3.55	16.0	.27	5.24	1.26		4.37	6.50	.81
FAGA231	12618	165.4	167.6	2.2		4A4	3.22	.03	2.16	3.85	45.0	.41	2.23	1.74		6.01	3.97	.64
FAGA231	12619	172.4	173.7	1.3		4A0	3.16	.01	1.12	3.02	34.0	.21	1.61	1.36		4.14	2.97	.73
FAGA231	12620	173.7	174.9	1.2		4A4	3.25	.01	1.75	6.71	46.0	.21	1.60	2.80		8.46	4.40	.79
FAGA225	12621	147.7	148.5	.8	100	4C7	3.78	.17	1.74	1.89	25.0	.14	11.70	9.13		3.63	20.83	.52
FAGA225	12622	148.5	149.1	.6	83	4D4*	3.89	.37	2.31	2.52	31.0	.14	11.10	9.84		4.83	20.94	.52
FAGA225	12623	149.1	150.1	1.0	90	4E47	4.43	.28	5.25	6.20	62.0	.21	15.50	14.30		11.45	29.80	.54
FAGA225	12624	150.1	151.1	1.0	100	4C*	3.44	.19	1.32	.95	18.0	.07	7.95	5.75		2.27	13.70	.42
FAGA225	12625	151.1	152.8	1.7	88	4L35		.12	.58	.62	9.0					1.20		.52
FAGA225	12627	156.7	157.1	.4	100	4E4@		.14	2.10	2.97	28.0					5.07		.59
FAGA232	12628	75.6	77.1	1.5	100	4C0		.05	2.16	2.15	31.0					4.31		.50

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAO	PB+ZN	PC+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGA232	12629	89.4	91.5	2.1	95	4A0	3.33	.02	1.18	2.19	22.0	.14	2.89	3.06		3.37	5.95	.65
FAGA232	12630	91.5	92.8	1.3	92	4A0	3.29	.02	1.00	1.82	20.0	.34	4.96	3.27		2.82	8.23	.65
FAGA232	12631	97.1	100.9	3.8	39	4A0	3.30	.02	.98	2.53	19.0	.21	3.39	4.46		3.51	7.85	.72
FAGA232	12632	107.3	108.8	1.5	93	4A0	3.43	.03	1.53	2.94	35.0	.55	8.80	1.40		4.47	10.20	.66
FAGA232	12633	108.8	110.2	1.4	93	4A4	3.36	.02	2.00	3.81	45.0	.55	8.00	2.00		5.81	10.00	.66
FAGA232	12634	115.6	116.1	.5	100	4C0		.01	.99	2.76	18.0					3.75		.74
FAGA232	12635	118.7	120.7	2.0	100	5D*		.01	.59	1.78	12.0					2.37		.75
FAGA232	12636	121.6	123.0	1.4	93	4A4	3.20	.02	1.14	6.41	37.0	.21	2.70	1.30		7.55	4.00	.85
FAGA232	12637	123.0	124.4	1.4	93	4A4	3.19	.01	1.77	6.41	43.0	.14	1.82	1.32		8.18	3.14	.78
FAGA232	12638	124.4	126.4	2.0	100	4D4	3.36	.01	3.04	10.00	63.0	.07	.78	2.07		13.04	2.85	.77
FAGA232	12639	126.4	127.9	1.5	100	4D0	3.19	.01	1.64	8.00	23.0	.07	1.86	1.77		9.64	3.63	.83
FAGA232	12640	127.9	129.9	2.0	100	4A4	3.16	.01	1.64	6.35	34.0	.07	1.59	1.08		7.99	2.67	.79
FAGA232	12641	129.9	131.6	1.7	100	4A4	3.24	.02	1.48	5.04	31.0	.21	4.39	1.46		6.52	5.85	.77
FAGA232	12642	132.7	135.3	2.6	58	4A4	3.40	.01	2.67	7.00	53.0	.27	8.58	2.52		9.67	11.10	.72
FAGA232	12643	135.3	137.9	2.6	27	4A4	3.26	.01	2.40	5.70	54.0	.14	1.81	1.14		8.10	2.95	.70
FAGA232	12644	139.3	141.3	2.0	95	4A4	3.21	.01	2.10	5.35	48.0	.21	.92	1.18		7.45	2.10	.72
FAGA232	12645	141.3	143.3	2.0	100	4A0	3.10	.01	1.41	3.89	28.0	.27	2.78	.97		5.30	3.75	.73
FAGA232	12646	143.3	145.3	2.0	100	4A4	3.28	.01	1.82	5.00	31.0	.41	4.00	.91		6.82	4.91	.73
FAGA232	12647	145.3	147.8	2.5	96	4A4	3.21	.01	2.22	6.24	42.0	.34	1.85	1.26		8.46	3.11	.74
FAGA232	12648	147.8	149.8	2.0	95	4A4	3.20	.01	1.75	4.09	39.0	.14	1.46	2.84		5.84	4.30	.70
FAGA232	12649	149.8	151.8	2.0	95	4A0	3.13	.02	1.01	3.39	21.0	.14	2.42	2.80		4.40	5.22	.77
FAGA232	12650	151.8	153.2	1.4	100	4A4	3.29	.02	2.12	5.83	44.0	.27	4.22	2.25		7.95	6.47	.73
FAGA232	12651	153.2	155.2	2.0	100	4A4	3.16	.02	1.51	4.09	30.0	.34	2.93	1.07		5.60	4.00	.73
FAGA232	12652	155.2	157.2	2.0	100	4A0	3.24	.04	2.12	2.73	30.0	.55	5.65	1.00		4.85	6.65	.56
FAGA232	12653	157.2	158.7	1.5	100	4A4	3.45	.02	2.30	5.26	39.0	.69	8.48	1.32		7.56	9.80	.70
FAGA232	12654	158.7	160.8	2.1	100	4A0	3.24	.04	1.36	2.62	26.0	.27	4.58	2.77		3.98	7.35	.66
FAGA232	12655	160.8	163.0	2.2	100	4A0	3.64	.03	1.05	3.08	22.0	.27	16.85	1.65		4.13	18.50	.75
FAGA232	12656	163.0	165.0	2.0	100	4A0	3.29	.03	1.42	3.31	25.0	.41	8.86	.94		4.73	9.80	.70
FAGA232	12657	165.0	167.0	2.0	100	4A4	3.34	.02	2.12	3.42	39.0	.48	8.64	1.08		5.54	9.72	.62
FAGA232	12658	167.0	168.9	1.9	100	4A4	3.08	.02	1.46	3.85	34.0	.21	2.18	.96		5.31	3.14	.73
FAGA232	12659	168.9	171.0	2.1	86	4A0	3.35	.02	1.75	2.58	33.0	.34	7.74	1.36		4.33	9.10	.60
FAGA232	12660	171.0	172.0	1.0	90	4A0	3.20	.02	1.61	2.35	31.0	.41	6.32	.88		3.96	7.20	.59
FAGA232	12661	172.0	174.1	2.1	95	4A0	3.60	.07	1.82	3.15	33.0	.48	15.30	1.70		4.97	17.00	.63
FAGA232	12662	174.1	175.1	1.0	100	4A34	3.55	.06	3.78	6.67	65.0	.62	11.00	2.08		10.45	13.08	.64
FAGA232	12663	175.1	177.0	1.9	89	5D4*	3.14	.02	.84	2.46	14.0	.01	.55	5.42		3.30	5.97	.75
FAGA232	12664	177.0	178.5	1.5	100	4A0	3.12	.01	1.06	3.54	18.0	.14	8.01	1.90		4.60	9.91	.77
FAGA232	12665	179.8	181.3	1.5	93	4A0	3.06	.01	.86	2.81	18.0	.07	1.07	2.30		3.67	3.37	.77
FAGA232	12666	181.3	182.8	1.5	93	4A0	3.10	.01	.61	.90	11.0	.01	2.62	1.03		1.51	3.65	.60
FAGA232	12667	182.8	184.8	2.0	100	4A4	3.12	.02	1.14	3.92	23.0	.07	2.69	2.00		5.06	4.69	.77
FAGA232	12668	184.8	186.8	2.0	70	4A0	3.14	.02	2.30	5.17	33.0	.48	2.09	1.10		7.47	3.19	.69
FAGA232	12669	186.8	188.8	2.0	85	4A0	3.10	.02	.99	3.85	23.0	.07	2.30	2.20		4.84	4.50	.80
FAGA232	12670	188.8	190.0	1.2	83	4A4	3.35	.01	.96	3.46	23.0	.07	2.69	2.18		4.42	4.87	.78
FAGA232	12671	190.0	191.5	1.5	67	4A4	3.12	.01	.96	2.26	13.0	.07	.73	4.29		3.22	5.02	.70
FAGA233	12672	102.4	106.7	4.3	100	4A0	3.17	.03	1.44	2.94	28.0	.20	3.67	8.00		4.38	11.67	.67
FAGA233	12673	108.1	108.5	.4	100	4E4	4.45	.05	3.98	8.61	64.0	.48	4.26	28.50		12.59	32.76	.68
FAGA233	12674	109.3	110.8	1.5	100	4A4D	3.21	.07	4.47	3.96	71.0	.48	2.42	9.10		8.43	11.52	.47
FAGA233	12675	110.8	113.0	2.2	100	4A4	3.04	.03	3.60	5.11	55.0	.48	1.84	4.60		8.71	6.44	.59
FAGA233	12676	113.0	115.1	2.1	100	4AC3	3.24	.04	2.37	3.36	44.0	.28	2.01	11.20		5.73	13.21	.59
FAGA233	12677	116.8	117.7	.9	100	4D0	3.08	.01	1.89	4.31	33.0	.14	4.85	5.20		6.20	10.05	.70
FAGA233	12678	121.0	122.6	1.6	100	4DE	3.45	.03	3.04	6.12	60.0	.48	7.80	9.40		9.16	17.20	.67

DDH	SAMPLE	---DEPTHS---		INT. REC M %	ROCK UNIT	S.G.	CU %	PB %	ZN %	AG G/MT	AU G/MT	PO %	PY %	BAO %	PB+ZN %	PO+PY %	ZN RATIO	
		FROM	TO															
FAGA233	12679	123.0	124.2	1.2	100	4E4	3.92	.07	8.50	10.30	138.0	.48	7.50	14.40		18.80	21.90	.55
FAGA233	12680	124.7	125.1	.4	100	4D4	3.40	.07	6.77	10.00	89.0	.34	5.81	5.10		16.77	10.91	.60
FAGA233	12681	127.0	128.6	1.6	100	4A4	3.02	.02	2.28	6.94	46.0	.28	2.85	3.30		9.22	6.15	.75
FAGA233	12682	130.1	131.4	1.3	100	4E0	4.40	.01	.28	1.59	14.0	.20	3.96	36.80		1.87	40.76	.85
FAGA233	12683	134.1	134.8	.7	100	4EA	4.30	.04	11.27	16.50	209.0	1.17	2.65	18.00		27.77	20.65	.59
FAGA233	12684	159.1	160.8	1.7	71	4DEA	3.51	.05	7.20	12.10	133.0	.48	4.49	8.40		19.30	12.89	.63
FAGA233	12685	169.1	170.2	1.1	100	4E4	3.50	.02	1.83	4.58	36.0	.48	3.59	15.30		6.41	18.89	.71
FAGA233	12686	170.2	173.6	3.4	100	4A4	2.98	.02	1.42	3.70	25.0	.34	3.28	3.04		5.12	6.32	.72
FAGA233	12687	175.5	177.4	1.9	100	4A4	3.23	.05	4.18	5.51	87.0	.68	1.84	7.90		9.69	9.74	.57
FAGA233	12688	177.4	179.4	2.0	100	4A4	3.50	.08	5.36	8.96	128.0	.82	1.69	9.80		14.32	11.49	.63
FAGA233	12689	180.9	184.1	3.2	87	4A0	2.99	.01	.85	1.45	15.0	.21	2.45	5.20		2.30	7.65	.63
FAGA234	12690	76.6	79.1	2.5	100	4E4	4.33	.01	1.66	5.42	29.0	.89	2.46	30.40		7.08	32.86	.77
FAGA234	12691	79.8	80.1	.3	100	4E4		.03	3.70	7.91	57.0					11.61		.68
FAGA234	12692	83.7	84.0	.3	100	4E0		.02	.84	1.62	17.0					2.46		.66
FAGA234	12693	84.0	86.9	2.9	79	4A0		.02	.94	1.55	18.0					2.49		.62
FAGA234	12694	86.9	89.1	2.2	100	4ED	3.75	.06	7.64	13.50	134.0	1.17	2.45	12.80		21.14	15.25	.64
FAGA234	12695	91.1	91.8	.7	71	4D4		.03	5.16	9.30	116.0					14.46		.64
FAGA234	12696	96.3	98.1	1.8	78	4DA	3.46	.09	3.90	5.07	58.0	1.30	2.25	14.30		8.97	16.55	.57
FAGA234	12697	103.8	105.0	1.2	92	4DE4	4.08	.10	8.10	15.20	128.0	.96	3.56	17.40		23.30	20.96	.65
FAGA234	12698	105.0	107.5	2.5	100	4DA	3.02	.02	1.90	4.98	30.0	.41	3.18	3.65		6.88	6.83	.72
FAGA234	12699	110.4	112.6	2.2	82	4D4	3.57	.06	7.42	11.00	152.0	.55	6.50	5.30		18.42	11.80	.60
FAGA234	12700	112.6	114.6	2.0	100	4A0	3.02	.02	1.66	2.91	31.0	.62	5.30	2.38		4.57	7.68	.64
FAGA234	12701	120.6	125.0	4.4	43	4A0	3.07	.02	.64	1.24	16.0	.21	1.78	7.80		1.88	9.58	.66
FAGA234	12702	125.5	128.2	2.7	100	4A4	2.91	.02	3.13	2.91	33.0	.48	1.78	1.64		6.04	3.42	.48
FAGA235	12703	61.6	63.9	2.3	100	4A4	2.93	.02	1.51	4.67	37.0	.27	1.47	1.44		6.18	2.91	.76
FAGA235	12704	67.4	68.0	.6	83	4C0	2.94	.02	.80	3.17	22.0	.14	3.84	1.34		3.97	5.18	.80
FAGA235	12705	68.0	69.9	1.9	95	4A4	2.89	.05	1.59	4.62	49.0	.21	1.65	2.20		6.21	3.85	.74
FAGA235	12706	69.9	72.8	2.9	62	4AD	2.95	.02	2.48	4.13	44.0	.34	1.48	2.86		6.61	4.34	.62
FAGA235	12707	72.8	75.3	2.5	100	4A4	3.06	.04	2.80	5.78	48.0	.41	1.10	4.82		8.58	5.92	.67
FAGA235	12708	75.3	77.0	1.7	100	4C5	2.98	.06	.92	1.23	15.0	.55	1.31	6.00		2.15	7.31	.57
FAGA235	12709	77.0	78.9	1.9	100	4C5	2.93	.04	1.82	1.90	29.0	.55	.98	4.38		3.72	5.36	.51
FAGA235	12710	78.9	80.7	1.8	83	4A0	2.95	.05	.98	1.50	16.0	.41	.80	4.99		2.48	5.79	.61
FAGA235	12711	136.7	137.2	.5	100	4E4		.03	2.72	9.80	47.0					12.52		.78
FAGA235	12712	138.3	139.1	.8	100	4E4	4.59	.02	4.26	6.06	94.0	1.10	1.64	31.90		10.32	33.54	.59
FAGA235	12713	139.1	142.0	2.9	100	4A4	3.16	.04	2.32	4.76	43.0	.34	4.12	5.70		7.08	9.82	.67
FAGA235	12714	142.0	143.7	1.7	100	4A0	2.97	.04	1.10	1.60	23.0	.27	2.03	3.87		2.70	5.90	.59
FAGA235	12715	143.7	145.7	2.0	95	4A4	2.99	.02	1.80	3.62	40.0	.48	1.30	4.14		5.42	5.44	.67
FAGA235	12716	146.0	148.4	2.4	63	4A0		.02	1.04	2.15	20.0					3.19		.67
FAGA235	12717	159.6	160.8	1.2	92	4AE0		.02	.97	2.85	17.0					3.82		.75
FAGA235	12718	165.7	166.4	.7	86	4A0		.02	.83	3.12	20.0					3.95		.79
FAGA235	12719	166.7	168.4	1.7	100	3G46		.04	.40	.40	9.0					.80		.50
FAGA236	12720	65.6	67.6	2.0	100	4A4	3.27	.04	1.93	3.08	39.0	.41	8.40	1.70		5.01	10.10	.61
FAGA236	12721	67.6	69.6	2.0	100	4A0	3.08	.04	.44	.69	11.0	.34	5.74	1.51		1.13	7.25	.61
FAGA236	12722	69.6	71.6	2.0	100	4A0	2.96	.03	1.08	1.62	19.0	.34	4.04	1.96		2.70	6.00	.60
FAGA236	12723	71.6	73.8	2.2	91	4A4	3.06	.03	1.80	3.92	32.0	.48	6.04	1.06		5.72	7.10	.69
FAGA236	12724	73.8	75.6	1.8	100	4C0	3.00	.03	1.18	3.20	22.0	.34	3.65	2.67		4.38	6.32	.73
FAGA236	12725	75.6	77.4	1.8	100	4C0	3.10	.03	1.25	2.91	22.0	.62	4.54	2.00		4.16	6.54	.70
FAGA236	12726	77.4	79.2	1.8	100	4D0	3.17	.05	1.89	3.83	29.0	.48	9.10	1.70		5.72	10.80	.67
FAGA236	12727	88.1	89.2	1.1	100	4AD	3.06	.05	2.29	4.22	32.0	.27	2.66	2.16		6.51	4.82	.65
FAGA236	12728	93.9	95.3	1.4	100	4A4	3.10	.02	1.60	4.18	28.0	.27	4.28	2.97		5.78	7.25	.72

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAO	PB+ZN	PC+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGA236	12729	95.3	96.9	1.6	100	4A0	2.95	.02	1.62	2.81	25.0	.34	3.55	.91		4.43	4.46	.63
FAGA236	12730	96.9	98.5	1.6	100	4A0	2.96	.02	1.08	3.24	20.0	.27	2.75	2.10		4.32	4.85	.75
FAGA236	12731	98.5	99.3	.8	100	4D0	2.97	.02	1.30	3.08	24.0	.14	1.59	2.76		4.38	4.35	.70
FAGA236	12732	100.3	101.0	.7	100	4A0	3.09	.02	2.69	5.80	46.0	.14	2.10	3.05		8.49	5.15	.68
FAGA236	12733	101.0	103.1	2.1	100	4A4	3.10	.06	2.15	3.15	36.0	.27	5.57	1.60		5.30	7.17	.59
FAGA236	12734	103.1	105.2	2.1	86	4A0	3.11	.05	1.70	3.09	33.0	.41	5.51	1.39		4.79	6.90	.65
FAGA236	12735	105.2	107.3	2.1	57	4A4	3.08	.04	3.01	7.60	61.0	.55	2.97	1.17		10.61	4.14	.72
FAGA236	12736	107.3	109.4	2.1	48	4A4	3.01	.04	2.37	5.10	44.0	.41	2.50	1.31		7.47	3.81	.68
FAGA236	12737	109.4	110.6	1.2	100	4D0	3.05	.04	1.78	4.28	32.0	.55	3.08	3.00		6.06	6.08	.71
FAGA236	12738	110.6	111.5	.9	11	4A4	2.98	.04	1.94	4.31	36.0	.07	1.40	3.25		6.25	4.65	.69
FAGA236	12739	111.5	112.8	1.3	85	4A4	3.09	.03	2.42	4.87	36.0	.07	3.01	3.56		7.29	6.57	.67
FAGA236	12740	112.8	114.0	1.2	100	4A0	3.01	.03	1.59	3.58	27.0	.01	1.35	3.62		5.17	4.97	.69
FAGA236	12741	114.6	117.0	2.4	100	4D4	3.20	.04	3.23	6.50	50.0	.21	5.33	2.62		9.73	7.95	.67
FAGA236	12742	117.0	118.5	1.5	100	4E4	4.28	.05	3.33	8.10	67.0	.75	24.40	4.00		11.43	28.40	.71
FAGA236	12743	119.2	120.1	.9	11	4E0		.01	.30	1.42	17.0					1.72		.83
FAGA236	12744	122.5	124.0	1.5	93	4C0	2.96	.05	1.63	2.25	25.0	.14	3.73	3.02		3.88	6.75	.58
FAGA236	12745	124.0	126.4	2.4	83	4A4	3.16	.04	2.14	3.23	36.0	.62	9.40	.80		5.37	10.20	.60
FAGA236	12746	126.4	128.8	2.4	92	4A4	3.10	.04	2.13	3.68	33.0	.75	5.56	.77		5.81	6.33	.63
FAGA236	12747	128.8	131.2	2.4	87	4A4	3.16	.05	3.02	2.60	43.0	1.30	7.52	.73		5.62	8.25	.46
FAGA236	12748	131.2	133.8	2.6	85	4A0	3.05	.15	1.78	2.60	29.0	.62	7.03	.95		4.38	7.98	.59
FAGA236	12749	134.7	136.2	1.5	87	4A34		.03	4.03	4.88	71.0					8.91		.55
FAGA236	12750	136.8	138.1	1.3	92	4DA		.04	2.40	4.29	40.0					6.69		.64
FAGA236	12751	138.9	140.5	1.6	100	4A4	3.12	.02	3.04	6.30	52.0	.69	6.70	1.30		9.34	8.00	.67
FAGA236	12752	140.5	142.2	1.7	100	4A4	2.96	.02	1.94	4.94	39.0	.21	1.88	1.31		6.88	3.19	.72
FAGA236	12753	142.2	143.4	1.2	92	3G96	2.96	.02	1.48	1.75	24.0	.27	1.08	1.57		3.23	2.65	.54
FAGA236	12754	143.4	144.8	1.4	100	3G46	2.94	.15	1.25	2.21	15.0	.27	1.61	1.64		3.46	3.25	.64
FAGA236	12755	146.1	147.0	.9	78	4CH		.02	2.24	3.78	44.0					6.02		.63
FAGA236	12756	147.0	148.1	1.1	100	3G96		.03	.70	2.20	13.0					2.90		.76
FAGA236	12757	154.8	156.1	1.3	100	4D5		.05	1.43	2.32	24.0					3.75		.62
FAGA236	12758	157.1	158.1	1.0	100	5D4*9		.03	.80	1.02	14.0					1.82		.56
FAGA236	12759	158.1	160.1	2.0	100	4C5	3.10	.05	1.62	3.13	30.0	.41	2.95	5.00		4.75	7.95	.66
FAGA236	12760	161.9	164.0	2.1	100	4A4	3.16	.03	2.54	4.43	43.0	.48	2.60	7.40		6.97	10.00	.64
FAGA236	12761	164.0	166.1	2.1	90	4A4	3.16	.04	2.21	5.10	36.0	.48	1.87	5.40		7.31	7.27	.70
FAGA236	12762	290.9	292.4	1.5	100	4G4#	4.16	.12	4.82	9.32	97.0	1.03	1.19	18.60		14.14	19.79	.66
FAGA236	12763	357.3	359.0	1.7	100	4EGL	3.92	.09	3.91	5.23	54.0	.69	2.70	13.00		9.14	15.70	.57
FAGA236	12764	360.0	361.1	1.1	91	4G4	4.57	.15	6.23	6.62	89.0	1.51	3.89	21.10		12.85	24.99	.52
FAGA236	12765	361.1	363.0	1.9	95	4E0*	4.64	.24	1.66	1.25	24.0	1.65	5.40	35.20		2.91	40.60	.43
FAGA236	12766	363.5	364.7	1.2	92	4ELD		.12	.68	.47	13.0					1.15		.41
FAGA236	12767	364.7	365.9	1.2	100	4G4	4.50	.11	5.24	5.93	66.0	.96	5.10	18.20		11.17	23.30	.53
FAGA236	12768	365.9	367.9	2.0	100	4C79	3.75	.27	1.26	1.87	22.0	.21	10.50	17.10		3.13	27.60	.60
FAGA236	12769	367.9	369.8	1.9	100	4C79	3.38	.37	.76	1.85	17.0	.27	7.70	9.10		2.61	16.80	.71
FAGA238	12770	48.5	49.9	1.4	71	4C5		.01	.24	.33	8.0					.57		.58
FAGA238	12771	49.9	51.6	1.7	94	4C5	3.06	.06	.82	1.95	20.0	.21	9.42	1.58		2.77	11.00	.70
FAGA238	12772	51.6	54.5	2.9	69	4C5	3.08	.08	.61	1.60	16.0	.21	8.53	.94		2.21	9.47	.72
FAGA238	12773	54.5	56.5	2.0	100	4C5	3.02	.09	.56	1.63	16.0	.34	9.62	.88		2.19	10.50	.74
FAGA238	12774	56.5	58.5	2.0	90	4C5	3.09	.07	.54	1.89	17.0	.34	8.95	.85		2.43	9.80	.78
FAGA238	12775	58.5	61.3	2.8	79	4C5	2.98	.06	1.00	1.97	21.0	.48	4.61	.90		2.97	5.51	.66
FAGA238	12776	61.3	63.3	2.0	95	3G14		.03	.20	.31	6.0					.51		.61
FAGA238	12777	63.3	65.8	2.5	92	3G14		.08	.77	1.45	16.0					2.22		.65
FAGA238	12778	65.8	67.8	2.0	100	4L14		.05	.62	.88	13.0					1.50		.59



DDH	SAMPLE	---DEPTHS---	INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PC	PY	SAO	PB+ZN	PC+PY	ZN
		FROM	TO	M	%	UNIT	%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGA240	12830	84.1	86.3	2.2	91	4C5	3.12	.04	1.25	3.22	27.0	.55	1.45	8.80	4.47	10.25	.72
FAGA240	12831	86.3	87.8	1.5	67	4C5	3.12	.06	1.23	2.94	28.0	.55	1.45	8.80	4.17	10.25	.71
FAGA240	12832	87.8	89.6	1.8	100	4C5	3.00	.04	1.48	3.42	29.0	.48	1.10	4.70	4.90	5.80	.70
FAGA240	12833	90.7	92.4	1.7	71	4C5	3.09	.03	1.20	3.73	29.0	.62	1.28	7.10	4.93	8.38	.76
FAGA240	12834	92.4	93.9	1.5	93	4D5	3.16	.03	1.55	4.98	33.0	.55	2.38	8.20	6.53	10.58	.76
FAGA240	12835	93.9	95.0	1.1	82	4D5	3.35	.05	1.00	4.85	26.0	.55	2.91	12.70	5.85	15.61	.83
FAGA240	12836	95.0	96.9	1.9	100	4DEA	3.83	.06	4.58	9.70	78.0	.96	2.65	17.80	14.28	20.45	.68
FAGA240	12837	96.9	98.8	1.9	89	4DEA	3.82	.09	2.58	8.00	49.0	1.32	3.30	20.20	10.58	23.50	.76
FAGA240	12838	98.8	100.3	1.5	100	4DEA	3.69	.08	3.18	7.50	52.0	1.23	2.41	18.80	10.68	21.21	.70
FAGA240	12839	100.3	101.8	1.5	100	4CEA	3.76	.11	.73	2.58	22.0	1.78	3.07	22.70	3.31	25.77	.78
FAGA240	12840	105.7	108.1	2.4	96	4EA4	3.88	.12	5.10	9.40	92.0	1.51	2.04	20.20	14.50	22.24	.65
FAGA240	12841	108.1	110.0	1.9	95	4A0	3.27	.13	1.11	2.89	31.0	.96	1.61	14.10	4.00	15.71	.72
FAGA239	12842	53.9	57.9	4.0	68	4A4	2.95	.02	1.53	4.82	29.0	.27	1.02	1.21	6.35	2.23	.76
FAGA239	12843	57.9	59.3	1.4	93	4A4	3.04	.03	3.08	6.70	62.0	.27	3.02	1.15	9.78	4.17	.69
FAGA239	12844	59.3	62.8	3.5	69	4E4	4.27	.14	8.20	12.60	153.0	1.44	17.82	3.88	20.80	21.70	.61
FAGA239	12845	62.8	64.0	1.2	100	4A0	3.11	.03	.66	2.60	12.0	.21	2.99	5.90	3.26	8.89	.80
FAGA239	12846	64.0	68.6	4.6	41	4A4	3.10	.02	1.18	3.88	22.0	.41	2.09	3.13	5.06	5.22	.77
FAGA120	12847	102.4	104.8	2.4	79	4C0	2.88	.02	1.75	3.01	27.0	.21	1.63	1.25	4.76	2.88	.63
FAGA120	12848	108.7	110.7	2.0	100	4D0	3.06	.04	1.91	3.25	32.0	.14	3.84	4.35	5.16	8.19	.63
FAGA120	12849	110.7	112.7	2.0	100	4D0	3.10	.04	2.35	4.72	40.0	.34	3.83	5.27	7.07	9.10	.67
FAGA120	12850	112.7	115.2	2.5	100	4D0	3.05	.05	3.07	5.30	50.0	.27	3.64	3.46	8.37	7.10	.63
FAGA120	12851	116.8	119.2	2.4	83	4D0	3.01	.02	2.73	4.87	48.0	.41	3.11	2.54	7.60	5.65	.64
FAGA120	12852	120.8	122.8	2.0	90	4A4	2.96	.02	1.69	3.59	29.0	.55	.84	3.34	5.28	4.18	.68
FAGA120	12853	122.8	125.1	2.3	61	4A4	3.29	.11	3.50	6.43	52.0	1.51	1.30	8.40	9.93	9.70	.65
FAGA120	12854	127.1	130.4	3.3	55	4C5		.09	.92	1.11	13.0				2.03		.55
FAGA120	12855	134.5	136.2	1.7	100	4A0		.04	1.52	2.69	24.0				4.21		.64
FAGA120	12856	136.5	138.0	1.5	100	4D5	3.24	.12	2.71	2.61	31.0	.07	5.90	7.60	5.32	13.50	.49
FAGA120	12857	138.0	139.6	1.6	94	4D5	3.00	.05	2.20	3.53	20.0	.01	3.00	2.61	5.73	5.61	.62
FAGA120	12858	139.6	140.7	1.1	100	4D0	3.07	.03	3.05	6.30	43.0	.07	3.34	2.95	9.35	6.29	.67
FAGA120	12859	140.7	141.5	.8	100	4ED6	3.68	.16	4.13	7.40	71.0	.48	2.88	15.80	11.53	18.68	.64
FAGA120	12860	142.1	143.8	1.7	100	4D0	2.93	.03	2.87	6.00	32.0	.14	1.79	.96	8.87	2.75	.68
FAGA120	12861	143.8	145.5	1.7	100	4D4	3.12	.05	4.53	7.30	61.0	1.03	3.15	2.80	11.83	5.95	.62
FAGA120	12862	146.7	147.4	.7	100	4D0		.03	2.59	4.50	42.0				7.09		.63
FAGA120	12863	151.7	153.6	1.9	100	4D0	2.97	.04	2.82	4.58	42.0	.21	2.35	1.78	7.40	4.13	.62
FAGA120	12864	153.6	155.6	2.0	100	4D0	3.02	.04	2.62	5.50	38.0	.21	2.24	2.52	8.12	4.76	.68
FAGA120	12865	156.0	156.6	.6	50	4C0		.03	1.75	3.18	28.0				4.93		.65
FAGA120	12866	162.2	164.2	2.0	100	4D0	2.99	.01	2.15	4.77	32.0	.21	2.39	2.08	6.92	4.47	.69
FAGA120	12867	165.5	167.5	2.0	100	4A0	3.06	.05	1.37	1.93	24.0	.55	.83	7.40	3.30	8.23	.58
FAGA120	12868	167.5	169.5	2.0	100	4A0	3.07	.04	1.25	1.88	22.0	.62	.75	7.00	3.13	7.75	.60
FAGA120	12869	169.5	171.5	2.0	100	4A0	3.09	.06	1.84	2.98	32.0	.48	1.10	6.50	4.82	7.60	.62
FAGA120	12870	171.5	173.5	2.0	95	4A4	3.19	.06	2.29	3.76	40.0	.62	1.09	7.70	6.05	8.79	.62
FAGA120	12871	173.5	175.3	1.8	100	4D5	3.09	.05	2.53	3.77	42.0	.89	1.78	4.51	6.30	6.29	.60
FAGA120	12872	175.3	177.0	1.7	100	4A4	3.14	.06	2.19	6.20	38.0	.41	1.23	5.30	8.39	6.53	.74
FAGA120	12873	177.0	178.6	1.6	100	4A4	3.01	.03	1.58	4.71	28.0	.27	1.09	2.96	6.29	4.05	.75
FAGA120	12874	178.6	180.3	1.7	100	4A4	3.04	.04	1.75	3.67	37.0	.27	1.53	3.47	5.42	5.00	.68
FAGA120	12875	183.3	184.5	1.2	75	4D0	3.27	.03	3.17	5.57	42.0	.48	5.77	3.55	8.74	9.32	.64
FAGA120	12876	185.8	186.9	1.1	100	4A43	3.43	.02	2.73	6.90	52.0	.62	11.00	1.80	9.63	12.80	.72
FAGA120	12877	189.3	191.3	2.0	100	4D34	3.52	.09	4.52	6.90	74.0	.62	5.20	9.40	11.42	14.60	.60
FAGA120	12878	191.5	192.0	.5	100	4D7	3.59	.19	4.42	3.50	73.0	1.03	12.10	8.70	7.92	20.80	.44
FAGA120	12879	193.2	194.0	.8	100	4A43		.04	3.06	7.50	61.0				10.56		.71

DDH	SAMPLE	---DEPTHS---	INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAO	PB+ZN	PG+PY	ZN
		FROM TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGA120	12880	201.7 202.9	1.2	100	4AD		.04	2.44	3.35	34.0					5.79		.58
FAGA120	12881	220.8 223.1	2.3	100	4A43	3.17	.03	5.20	8.20	90.0	.34	2.53	9.20		13.40	11.73	.61
FAGA120	12882	223.3 224.3	1.0	100	4A43	3.52	.23	4.61	6.70	75.0	.69	1.11	12.20		11.31	13.31	.59
FAGA120	12883	224.6 228.1	3.5	100	5A19		.02	.56	1.33	13.0					1.89		.70
FAGA120	12884	307.0 308.4	1.4	100	4EG4	3.91	.05	7.40	16.00	126.0	.69	1.83	12.10		23.40	13.93	.68
FAGA120	12885	308.4 309.7	1.3	85	4E45	4.06	.06	5.20	10.10	93.0	.75	1.35	17.60		15.30	18.95	.66
FAGA120	12886	312.0 313.3	1.3	85	4D45	3.67	.08	5.80	9.70	87.0	.75	1.65	17.80		15.50	19.45	.63
FAGA120	12887	314.0 314.5	.5	80	4D45	3.68	.03	6.20	10.10	95.0	.75	2.00	11.30		16.30	13.30	.62
FAGA120	12888	314.5 317.3	2.8	39	4A34	3.54	.05	4.72	3.99	65.0	1.37	1.43	14.10		8.71	15.53	.46
FAGA120	1289C	318.4 319.7	1.3	92	4A4		.08	4.81	5.50	85.0					10.31		.53
FAGA120	12891	320.7 322.5	1.8	33	4A4	3.42	.04	4.08	7.10	75.0	.41	1.17	9.40		11.18	10.57	.64
FAGA120	12892	322.5 324.3	1.8	89	4A4	3.43	.04	4.00	6.10	71.0	.48	1.14	10.40		10.10	11.54	.60
FAGA120	12893	324.3 326.1	1.8	100	4A4	3.45	.09	3.57	5.70	70.0	.75	1.07	11.90		9.27	12.97	.61
FAGA120	12894	326.1 327.9	1.8	100	4A4	3.43	.05	4.04	6.30	70.0	.41	1.99	8.90		10.34	10.89	.61
FAGA120	12895	335.1 336.3	1.2	67	4E64		.12	3.39	5.00	69.0					8.39		.60
FAGA120	12896	375.2 377.9	2.7	85	4A0		.23	.15	.17	10.0					.32		.53
FAGA120	12897	377.9 380.7	2.8	100	4A0		.15	.04	.07	5.0					.11		.64
FAGA120	12898	380.7 382.1	1.4	86	4E0	4.32	.14	5.20	11.10	77.0	.84	1.81	22.20		16.30	24.01	.68
FAGA120	12899	384.9 387.3	2.4	100	4A7\$		.11	.05	.10	3.0					.15		.67
FAGA120	12900	387.3 389.7	2.4	96	4A7\$		.10	.11	.13	5.0					.24		.54
FAGA120	12901	389.7 390.4	.7	100	4C5\$7		.11	1.43	1.73	30.0					3.16		.55
FAGA120	12902	390.4 391.1	.7	100	4A79		.09	.06	.05	4.0					.11		.46
FAGA120	12903	392.1 393.9	1.8	50	4ADE		.10	2.56	3.91	45.0					6.47		.60
FAGA120	12904	403.8 405.1	1.3	92	4EG@4	4.25	.08	5.01	7.90	75.0	.75	16.74	2.06		12.91	18.80	.61
FAGA120	12905	405.1 407.5	2.4	100	4E8	4.61	.35	1.17	1.16	27.0	1.23	26.80	11.40		2.33	38.20	.50
FAGA120	12906	407.5 408.5	1.0	90	4G4\$	4.35	.16	4.57	6.70	65.0	1.51	13.59	3.01		11.27	16.60	.59
FAGA124	12907	79.8 81.8	2.0	100	4A4	3.02	.04	2.19	4.41	41.0	.21	2.57	1.28		6.60	3.85	.67
FAGA124	12908	81.8 83.8	2.0	55	4A4	3.01	.03	2.03	3.66	35.0	.27	3.04	1.33		5.69	4.37	.64
FAGA124	12909	83.8 85.8	2.0	45	4A4	3.05	.01	2.16	4.99	40.0	.27	.93	1.26		7.15	2.19	.70
FAGA124	12910	85.8 87.8	2.0	65	4A0	2.93	.01	1.35	2.96	27.0	.07	1.06	.72		4.31	1.78	.69
FAGA124	12911	87.8 89.8	2.0	100	4A4	3.05	.02	1.91	4.95	39.0	.27	1.18	1.92		6.86	3.10	.72
FAGA124	12912	89.8 91.8	2.0	95	4A4	3.01	.02	1.98	4.64	40.0	.34	1.05	2.25		6.62	3.30	.70
FAGA124	12913	91.8 93.8	2.0	85	4A4	3.03	.04	2.96	7.65	57.0	.41	1.43	2.11		10.61	3.54	.72
FAGA124	12914	93.8 95.8	2.0	85	4A4	3.04	.03	2.58	4.82	44.0	.75	1.06	4.84		7.40	5.90	.65
FAGA124	12915	95.8 97.8	2.0	80	4A4	2.98	.05	2.71	4.76	42.0	.41	1.27	2.93		7.47	4.20	.64
FAGA124	12916	97.8 99.8	2.0	70	4A4	2.95	.02	2.16	4.85	35.0	.48	1.37	1.73		7.01	3.10	.69
FAGA124	12917	99.8 103.3	3.5	46	4A4	3.03	.03	2.83	4.71	45.0	.55	1.05	2.98		7.54	4.03	.62
FAGA124	12918	103.3 104.2	.9	100	4D5	3.00	.02	2.06	5.73	39.0	.34	2.95	1.35		7.79	4.30	.74
FAGA124	12919	104.2 106.2	2.0	85	4A4	2.93	.01	2.03	4.11	34.0	.41	1.23	2.05		6.14	3.28	.67
FAGA124	12920	106.2 108.2	2.0	85	4A0	3.09	.06	1.64	2.40	27.0	.69	.82	8.40		4.04	9.22	.59
FAGA124	12921	108.2 110.2	2.0	100	4A4	3.04	.07	2.58	3.76	41.0	.62	.87	5.50		6.34	6.37	.59
FAGA124	12922	110.2 112.2	2.0	90	4A0	3.00	.04	1.79	2.61	26.0	.62	.69	4.77		4.40	5.46	.59
FAGA124	12923	112.2 114.2	2.0	90	4A4	2.93	.03	1.91	3.47	26.0	.48	.85	2.83		5.38	3.68	.65
FAGA124	12924	114.2 116.1	1.9	84	4A4	2.94	.03	1.93	4.76	28.0	.69	1.32	1.99		6.69	3.31	.71
FAGA124	12925	116.1 117.5	1.4	100	4A4	2.88	.01	1.46	3.90	25.0	.34	1.09	1.04		5.36	2.13	.73
FAGA124	12926	117.5 119.5	2.0	85	4D5	2.91	.01	1.44	4.10	25.0	.34	1.30	1.02		5.54	2.32	.74
FAGA124	12927	119.5 121.5	2.0	90	4C5	2.91	.02	1.00	2.46	19.0	.34	1.12	2.46		3.46	3.58	.71
FAGA124	12928	121.5 124.4	2.9	76	4C5	2.92	.03	1.10	2.12	19.0	.34	1.01	2.64		3.22	3.65	.66
FAGA124	12929	128.4 130.4	2.0	85	4A4	3.10	.04	2.18	3.50	46.0	.62	1.38	7.40		5.68	8.78	.62
FAGA124	12930	130.4 132.4	2.0	90	4A4	3.33	.06	3.46	5.89	65.0	.69	1.56	9.20		9.35	10.76	.63

DDH	SAMPLE	---DEPTHS---	INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAO	PB+ZN	PC+PY	ZN
		FROM	TO	M	%	UNIT	%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGA124	12931	132.4	134.9	2.5	92	4A4	3.24	.03	2.62	4.47	51.0	.41	2.75	7.60	7.09	10.35	.63
FAGA124	12932	139.7	141.8	2.1	90	4A4	3.12	.02	2.80	6.20	53.0	.55	1.59	4.66	9.00	6.25	.69
FAGA124	12933	147.4	148.6	1.2	100	4A4		.01	2.57	4.93	47.0				7.50		.66
FAGA124	12934	203.1	204.1	1.0	90	4A34		.10	4.47	6.74	77.0				11.21		.60
FAGA124	12935	209.0	211.8	2.8	86	4AD	3.03	.03	2.51	4.67	34.0	.34	1.72	1.87	7.18	3.59	.65
FAGA124	12936	213.4	214.6	1.2	33	4A4		.02	3.09	5.61	63.0				8.70		.64
FAGA124	12937	222.2	224.7	2.5	80	4A0	3.07	.01	2.10	2.80	27.0	.34	1.63	5.50	4.90	7.13	.57
FAGA124	12938	314.3	315.8	1.5	100	4C5		.02	1.09	1.94	21.0				3.03		.64
FAGA124	12939	324.3	326.7	2.4	92	4AC	3.26	.07	.94	1.83	20.0	.34	1.34	12.20	2.77	13.54	.66
FAGA124	12940	387.1	389.1	2.0	95	4E8\$	4.55	.15	3.49	3.85	50.0	1.23	4.64	24.80	7.34	29.44	.52
FAGA124	12941	389.1	391.1	2.0	90	4E68	4.02	.28	2.99	2.43	39.0	.55	4.68	24.00	5.42	28.68	.45
FAGA124	12942	391.1	393.1	2.0	95	4E81	4.00	.32	.93	1.91	17.0	.62	5.59	23.20	2.84	28.79	.67
FAGA124	12943	393.1	395.1	2.0	95	4E14		.43	.50	.67	14.0				1.17		.57
FAGA124	12944	395.1	396.9	1.8	94	4E14		.33	.86	.96	21.0				1.82		.53
FAGA124	12945	396.9	398.9	2.0	85	4C3\$		.25	.72	1.42	15.0				2.14		.66
FAGA124	12946	398.9	400.6	1.7	76	4C3\$		.32	.83	1.69	16.0				2.52		.67
FAGA124	12947	400.6	402.6	2.0	70	4L14		.48	.75	.76	18.0				1.51		.50
FAGA124	12948	402.6	405.0	2.4	100	4L14		.27	.52	.65	12.0				1.17		.56
FAGU172	12949	.0	2.4	2.4	42	4A4	3.17	.01	3.48	6.50	68.0	.34	2.44	4.03	9.98	6.47	.65
FAGU172	12950	2.4	4.9	2.5	64	4E4	4.01	.04	6.80	16.40	154.0	.82	1.96	13.70	23.20	15.66	.71
FAGU172	12951	4.9	6.0	1.1	100	4A4	3.06	.01	2.72	4.46	66.0	.41	.91	3.63	7.18	4.54	.62
FAGU172	12952	6.0	6.6	.6	100	4E154	3.37	.01	3.65	12.50	73.0	.41	1.13	9.60	16.15	10.73	.77
FAGU172	12953	14.3	16.2	1.9	100	4A4	3.60	.04	7.10	14.00	142.0	1.17	2.01	8.80	21.10	10.81	.66
FAGU172	12954	16.2	18.1	1.9	100	4A4	3.39	.01	6.40	6.80	121.0	.55	1.78	7.20	13.20	8.98	.52
FAGU172	12955	18.1	20.0	1.9	100	4A4	3.23	.02	3.87	6.00	67.0	.41	2.47	5.30	9.87	7.77	.61
FAGU172	12956	20.0	21.9	1.9	89	4A4	3.24	.01	3.12	7.10	59.0	.27	.82	7.80	10.22	8.62	.69
FAGU172	12957	21.9	23.8	1.9	100	4A4		.02	3.68	4.10	70.0				7.78		.53
FAGU172	12958	23.8	25.7	1.9	100	4A4	3.10	.04	1.72	8.70	35.0	.27	.97	6.70	10.42	7.67	.84
FAGU172	12959	25.7	27.6	1.9	100	4A4	3.22	.01	3.35	5.60	61.0	.21	1.13	5.70	8.95	6.83	.63
FAGU172	12960	27.6	29.5	1.9	79	4A4	3.24	.01	2.22	4.05	43.0	.21	.91	8.20	6.27	9.11	.65
FAGU172	12961	29.5	31.4	1.9	100	4A4	3.14	.01	1.80	9.10	31.0	.21	1.16	5.80	10.90	6.96	.83
FAGU172	12962	31.4	33.2	1.8	100	4A4	3.45	.01	4.24	7.90	78.0	.48	1.45	10.40	12.14	11.85	.65
FAGU172	12963	35.5	37.3	1.8	100	4A4	3.35	.01	3.43	8.40	69.0	.14	1.21	9.60	11.83	10.81	.71
FAGU172	12964	37.3	39.0	1.7	100	4A4	3.22	.03	2.84	7.00	57.0	.41	1.04	8.30	9.84	9.34	.71
FAGU172	12965	39.0	40.5	1.5	100	4A4	3.67	.07	2.76	5.00	58.0	.89	1.89	16.30	7.76	18.19	.64
FAGU172	12966	40.9	41.4	.5	80	4E*		.05	.94	1.38	22.0				2.32		.60
FAGU172	12967	49.4	51.3	1.9	100	4A4	3.49	.05	5.10	7.00	81.0	.89	1.61	11.40	12.10	13.01	.58
FAGU172	12968	51.3	53.2	1.9	100	4A4	3.41	.06	6.80	10.10	105.0	.96	1.09	8.00	16.90	9.09	.60
FAGU172	12969	53.2	55.1	1.9	100	4A4	3.28	.03	4.06	8.80	71.0	.48	1.08	7.80	12.86	8.88	.68
FAGU172	12970	55.1	57.0	1.9	100	4A4	3.34	.02	2.73	6.50	53.0	.41	1.13	10.70	9.23	11.83	.70
FAGU172	12971	57.0	58.9	1.9	100	4A4	3.47	.03	4.83	8.60	87.0	.62	1.21	10.50	13.43	11.71	.64
FAGU172	12972	58.9	60.8	1.9	100	4A4	3.34	.03	2.03	3.74	39.0	.89	.97	12.20	5.77	13.17	.65
FAGU172	12973	60.8	62.7	1.9	100	4A0	3.39	.06	.48	1.27	12.0	.89	1.24	15.60	1.75	16.84	.73
FAGU172	12974	62.7	64.6	1.9	100	4A0		.05	.68	1.82	16.0				2.50		.73
FAGU172	12975	90.0	92.2	2.2	91	4L14		.02	.30	.63	6.0				.93		.68
FAGU172	12976	92.2	94.5	2.3	100	4L14		.10	.31	.44	8.0				.75		.59
FAGU172	12977	94.5	96.5	2.0	100	4A4	3.38	.12	3.03	3.96	51.0	1.03	1.28	12.80	6.99	14.08	.57
FAGU172	12978	96.5	98.5	2.0	100	4A4	3.42	.10	2.89	3.70	44.0	.82	.96	14.40	6.59	15.36	.56
FAGU172	12979	98.5	100.5	2.0	100	4A3	3.83	.12	1.91	2.11	40.0	.96	.93	16.70	4.02	17.63	.52
FAGU172	12980	100.5	102.5	2.0	100	4A3		.16	.48	.66	23.0				1.14		.58

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	FY	BAO	PB+ZN	PC+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGU172	12981	102.5	104.5	2.0	100	4A4	3.53	.07	3.59	3.78	43.0	.96	.89	8.10		7.37	8.99	.51
FAGU172	12982	104.5	106.5	2.0	100	4A0	3.73	.13	1.61	2.77	29.0	1.17	.99	13.30		4.33	14.29	.63
FAGU172	12983	106.5	108.5	2.0	100	4A34	3.83	.14	2.75	2.93	49.0	1.58	1.64	14.80		5.68	16.44	.52
FAGU172	12984	108.5	110.5	2.0	100	4A0	3.82	.14	1.11	2.19	25.0	1.37	1.25	16.90		3.30	18.15	.66
FAGU172	12985	110.5	112.5	2.0	100	4A0	3.52	.09	.83	1.16	19.0	1.03	.83	11.40		1.99	12.23	.58
FAGU172	12986	112.5	114.0	1.5	100	4A0	3.79	.11	2.67	.84	41.0	1.10	1.18	15.60		3.51	16.78	.24
FAGU172	12987	114.0	115.7	1.7	100	4A3		.20	.35	.62	22.0					.97		.64
FAGU172	12988	115.7	116.6	.9	100	4E4	5.18	.14	9.70	15.50	172.0	1.58	2.00	21.90		25.20	23.90	.62
FAGU172	12989	116.6	117.3	.7	100	4EG	5.36	.26	3.52	6.70	107.0	1.30	.46	27.20		10.22	27.66	.66
FAGU172	12990	117.3	118.7	1.4	100	4E4	4.62	.14	2.61	2.68	49.0	1.37	.82	36.00		5.29	36.82	.51
FAGU172	12991	118.7	120.1	1.4	100	4E0	4.78	.18	2.24	2.16	52.0	1.30	.72	39.10		4.40	39.82	.49
FAGU172	12992	120.1	121.9	1.8	100	4GE4	4.59	.17	4.16	8.70	74.0	1.44	2.08	25.60		12.86	27.68	.68
FAGU190	12993	4.5	6.5	2.0	90	4C5		.04	.86	1.69	14.0					2.55		.66
FAGU190	12994	6.5	8.5	2.0	70	4C5		.05	.94	1.61	13.0					2.55		.63
FAGU190	12995	8.5	10.6	2.1	90	4C5	3.03	.04	1.67	1.81	21.0	.41	.75	4.25		3.48	5.00	.52
FAGU190	12996	10.6	12.1	1.5	87	4C0	2.96	.02	2.55	2.29	34.0	.55	.88	3.20		4.84	4.08	.47
FAGU190	12997	12.1	13.7	1.6	94	4C0	2.91	.02	2.29	1.81	30.0	1.23	.80	2.44		4.10	3.24	.44
FAGU190	12998	13.7	15.6	1.9	100	4C5	2.92	.19	2.08	2.38	26.0	.21	2.67	3.38		4.46	6.05	.53
FAGU190	12999	28.0	29.8	1.8	89	4D0	2.94	.01	1.81	3.30	27.0	.27	1.86	1.79		5.11	3.65	.65
FAGU190	13000	29.8	31.2	1.4	93	4C5	2.91	.03	1.40	2.75	19.0	.27	1.82	2.06		4.15	3.88	.66
FAGU168	14001	.0	1.9	1.9		4A4	3.99	.13	5.80	16.10	138.0	1.65	1.17	17.60		21.90	18.77	.74
FAGU168	14002	1.9	3.8	1.9		4A4	3.08	.10	2.84	8.80	53.0	.48	.90	5.10		11.64	6.00	.76
FAGU168	14003	3.8	5.7	1.9		4A4	3.21	.02	4.03	9.40	74.0	.48	.84	7.30		13.43	8.14	.70
FAGU168	14004	5.7	7.6	1.9		4A4	3.10	.02	2.99	8.30	54.0	.21	.87	5.00		11.29	5.87	.74
FAGU168	14005	30.9	32.0	1.1		4E4S	4.02	.01	5.20	13.40	98.0	.48	1.90	18.60		18.60	20.50	.72
FAGU168	14006	33.5	34.0	.5		4K4	3.94	.01	4.41	9.40	84.0	.48	1.92	19.20		13.81	21.12	.68
FAGU168	14007	34.0	36.7	2.7		4A4	3.33	.02	3.74	6.80	71.0	.62	.97	11.00		10.54	11.97	.65
FAGU168	14008	36.7	38.1	1.4		4D3	3.63	.09	2.58	4.24	59.0	.75	5.55	16.30		6.82	21.85	.62
FAGU168	14009	109.5	110.0	.5		4L14		.03	.34	.16	7.0					.50		.32
FAGU168	14010	110.0	110.8	.8		4A0		.08	.23	.17	7.0					.40		.42
FAGU168	14011	110.8	113.9	3.1		4A1		.07	.53	.35	14.0					.88		.40
FAGU168	14012	113.9	114.6	.7		5D4*		.03	.16	.27	6.0					.43		.63
FAGU168	14013	114.6	116.6	2.0		4A1		.11	.84	.98	20.0					1.82		.54
FAGU168	14014	116.6	118.9	2.3		4E4	4.62	.18	4.42	8.00	90.0	1.23	.55	24.20		12.42	24.75	.64
FAGU168	14015	118.9	121.2	2.3		4G4	4.67	.05	5.20	9.60	92.0	.96	.36	16.40		14.80	16.76	.65
FAGU168	14016	121.2	123.4	2.2		4G4	4.65	.18	5.30	9.00	103.0	.96	.43	18.80		14.30	19.23	.63
FAGU168	14017	123.4	124.5	1.1		4E4	4.78	.26	4.03	6.50	103.0	1.30	.58	30.90		10.53	31.48	.62
FAGU168	14018	133.9	136.0	2.1		4EG	4.61	.32	2.47	2.45	46.0	1.51	1.00	36.60		4.92	37.60	.50
FAGU168	14019	136.0	138.1	2.1		4EG	4.78	.26	2.40	3.57	62.0	1.85	.80	35.60		5.97	36.40	.60
FAGU168	14020	138.1	140.3	2.2		4G4	4.67	.15	4.03	8.33	85.0	1.58	.50	24.20		12.36	24.70	.67
FAGU168	14021	140.3	142.4	2.1		4G4	4.73	.15	4.67	9.00	84.0	2.33	.35	17.50		13.67	17.85	.66
FAGU168	14022	142.4	144.5	2.1		4G4	4.59	.15	5.70	9.00	94.0	1.85	.58	23.40		14.70	23.98	.61
FAGU168	14023	144.5	145.3	.8		4A34	3.35	.06	2.48	4.32	45.0	.82	1.03	13.70		6.80	14.73	.64
FAGU168	14024	145.9	147.8	1.9		4A1		.06	.25	.67	11.0					.92		.73
FAGU168	14025	150.0	150.4	.4		4C0		.06	.12	.17	9.0					.29		.59
FAGU168	14026	150.4	152.5	2.1		4A0		.10	.84	1.41	22.0					2.25		.63
FAGU168	14027	152.5	154.1	1.6		4E46	4.48	.28	3.25	5.70	57.0	1.03	1.50	28.60		8.95	30.10	.64
FAGU168	14028	154.1	155.4	1.3		4D45	3.73	.21	3.94	8.60	81.0	2.06	2.33	18.70		12.54	21.03	.69
FAGU168	14029	155.4	156.5	1.1		4D4	3.75	.18	4.80	6.60	81.0	2.13	2.30	18.60		11.40	20.90	.58
FAGU162	14031	10.0	12.0	2.0	90	4A0	3.05	.05	1.97	.68	30.0	.75	1.90	6.90		2.65	8.80	.26

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAO	PB+ZN	PC+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGU162	14032	12.0	14.0	2.0	100	4AG	3.00	.06	.66	.31	14.0	.62	.75	7.30		.97	8.05	.32
FAGU162	14033	14.0	16.0	2.0	95	4A0	3.14	.07	1.41	1.15	24.0	.69	.81	11.20		2.56	12.01	.45
FAGU162	14034	16.0	18.0	2.0	85	4A0	3.10	.07	1.30	1.22	24.0	.75	1.23	8.90		2.52	10.13	.48
FAGU162	14035	18.0	19.6	1.6	94	4A0	3.03	.06	.87	.78	17.0	.55	.54	9.50		1.65	10.04	.47
FAGU162	14036	19.6	21.6	2.0	100	4C5	2.96	.05	.86	1.39	16.0	.41	.82	4.08		2.25	4.90	.62
FAGU162	14037	21.6	23.4	1.8	83	4C5	2.88	.05	1.16	2.41	20.0	.55	.84	3.11		3.57	3.95	.68
FAGU162	14038	23.4	25.0	1.6	63	4A0	3.27	.13	.93	2.28	19.0	1.71	.68	15.80		3.21	16.48	.71
FAGU162	14039	25.0	26.6	1.6	94	4A4	3.16	.07	2.19	3.68	40.0	1.10	.74	11.10		5.87	11.84	.63
FAGU162	14040	26.6	27.7	1.1	100	4E4	4.37	.21	3.94	5.90	86.0	1.37	1.15	29.90		9.84	31.05	.60
FAGU162	14041	34.5	35.7	1.2	92	4GL		.02	3.79	7.90	84.0					11.69		.68
FAGU162	14042	49.2	50.7	1.5	93	4G4	4.01	.03	6.10	11.80	128.0	.82	1.50	7.70		17.90	9.20	.66
FAGU162	14043	50.7	52.3	1.6	94	4G4	4.00	.16	7.40	15.10	131.0	1.85	1.98	9.90		22.50	11.88	.67
FAGU162	14044	52.3	54.0	1.7	100	4G4	4.35	.07	6.80	13.10	143.0	1.03	1.24	11.10		19.90	12.34	.66
FAGU162	14045	100.1	102.0	1.9	95	4AED	3.44	.18	2.01	2.85	30.0	1.99	3.38	17.10		4.86	20.48	.59
FAGU162	14046	102.0	104.0	2.0	100	4D0	3.51	.32	1.85	3.19	33.0	.96	4.68	17.00		5.04	21.68	.63
FAGU162	14047	104.0	105.7	1.7	88	4C0	3.53	.30	1.34	2.02	26.0	.89	4.54	17.80		3.36	22.34	.60
FAGU162	14048	105.7	107.6	1.9	89	4ALD	3.20	.12	1.76	2.50	32.0	.41	3.33	10.80		4.26	14.13	.59
FAGU162	14049	107.6	110.5	2.9	100	4C5		.23	.59	.69	14.0					1.28		.54
FAGU162	14050	110.5	112.8	2.3	83	4A0		.03	1.14	1.70	19.0					2.84		.60
FAGU162	14052	132.4	133.1	.7	100	4E4		.04	3.83	6.60	80.0					10.43		.63
FAGU162	14053	142.4	144.0	1.6	100	4GA	3.52	.05	1.89	3.69	37.0	.48	2.38	10.80		5.58	13.18	.66
FAGU162	14054	144.0	145.5	1.5	80	5C*	3.19	.01	.80	2.24	17.0	.34	3.60	6.80		3.04	10.40	.74
FAGU162	14055	145.5	147.2	1.7	94	4GH	4.52	.15	4.36	7.20	77.0	1.58	6.00	18.70		11.56	24.70	.62
FAGU166	14056	35.1	37.8	2.7	89	4EAC	3.46	.06	3.62	6.20	69.0	.82	1.10	13.00		9.82	14.10	.63
FAGU166	14057	37.8	40.2	2.4	100	4AC	3.35	.04	2.26	2.22	36.0	.89	.96	14.00		4.48	14.96	.50
FAGU166	14058	47.1	49.1	2.0	90	4C5	2.97	.05	.93	1.61	20.0	.75	.85	4.75		2.54	5.60	.63
FAGU166	14059	51.6	54.2	2.6	100	4C0	2.94	.04	.92	1.85	19.0	.55	1.43	3.82		2.77	5.25	.67
FAGU166	14060	113.5	115.3	1.8	100	4AG	3.73	.08	2.71	4.75	55.0	.75	1.08	13.90		7.46	14.98	.64
FAGU166	14061	115.3	117.3	2.0	100	4E4	4.36	.18	2.98	4.13	60.0	.55	1.20	28.50		7.11	29.70	.58
FAGU166	14062	117.3	119.3	2.0	90	4E4	4.33	.21	2.56	3.45	56.0	.62	1.56	30.20		6.01	31.76	.57
FAGU166	14063	119.3	120.2	.9	100	4E4	4.20	.16	2.96	4.75	71.0	1.03	.99	25.00		7.71	25.99	.62
FAGU166	14064	121.9	123.6	1.7	88	4A0		.08	1.03	1.60	20.0					2.63		.61
FAGU166	14065	130.3	132.3	2.0	100	4C0		.06	.35	.60	9.0					.95		.63
FAGU166	14066	132.3	134.3	2.0	100	4C0		.12	1.19	2.06	25.0					3.25		.63
FAGU166	14067	134.3	136.1	1.8	89	4C0		.05	.49	.84	12.0					1.33		.63
FAGU166	14068	138.3	140.0	1.7	100	4A30	3.29	.15	1.51	2.11	30.0	.96	1.13	15.30		3.62	16.43	.58
FAGU166	14069	140.0	141.7	1.7	100	4A34	3.52	.10	5.00	7.60	80.0	1.65	1.23	14.30		12.60	15.53	.60
FAGU166	14070	141.7	143.5	1.8	94	4A34	3.39	.24	3.44	4.32	55.0	1.03	1.74	13.70		7.76	15.44	.56
FAGU166	14071	143.5	145.9	2.4	100	4C3		.40	.57	.85	20.0					1.42		.60
FAGU166	14072	145.9	148.3	2.4	100	4C3		.42	.51	.59	22.0					1.10		.54
FAGU166	14073	148.3	150.9	2.6	54	4E0	4.67	.14	1.48	.88	34.0	.82	1.10	37.30		2.36	38.40	.37
FAGU166	14074	150.9	151.5	.6	100	4A4	3.56	.12	3.89	5.20	61.0	1.51	2.70	15.40		9.09	18.10	.57
FAGU158	14075	1.0	2.5	1.5		4A4	3.26	.03	2.73	5.40	50.0	.96	1.01	10.90		8.13	11.91	.66
FAGU158	14076	2.5	4.1	1.6		4A4	3.43	.10	2.91	5.00	53.0	1.23	.88	14.80		7.91	15.68	.63
FAGU158	14077	4.1	5.8	1.7		4A34	4.03	.21	6.10	7.90	118.0	1.44	1.17	23.20		14.00	24.37	.56
FAGU158	14078	5.8	7.6	1.8		4A34	4.25	.03	8.40	15.10	140.0	1.17	1.75	20.80		23.50	22.55	.64
FAGU158	14079	7.6	9.2	1.6		4A4	3.28	.01	5.20	11.30	86.0	.27	2.07	7.10		16.50	9.17	.68
FAGU158	14080	9.2	10.8	1.6		4A4	3.20	.02	2.11	4.16	44.0	.48	1.10	10.30		6.27	11.40	.66
FAGU158	14081	10.8	12.4	1.6		4A4	3.12	.09	3.40	5.50	58.0	.89	.67	7.60		8.90	8.27	.62
FAGU158	14082	12.4	14.1	1.7		4A4	3.64	.10	3.45	8.50	64.0	.75	1.24	15.60		11.95	16.84	.71

DDH	SAMPLE	---DEPTHS---	INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAO	PB+ZN	PC+PY	ZN
		FROM	TO	M	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGU158	14083	15.5	16.8	1.3	4A30		.05	1.48	2.73	32.0					4.21		.65
FAGU158	14085	39.5	42.7	3.2	4L24	3.42	.16	1.78	1.83	27.0	.21	10.00	8.10		3.61	18.10	.51
FAGU158	14087	42.7	45.7	3.0	4L42		.08	.74	.97	14.0					1.71		.57
FAGU158	14088	45.7	47.2	1.5	4GE	3.48	.15	5.60	6.30	102.0	.62	2.68	13.70		11.90	16.38	.53
FAGU158	14089	47.2	50.2	3.0	4L42		.03	.31	.20	7.0					.51		.39
FAGU158	14090	50.2	53.2	3.0	4L42		.09	.67	.57	13.0					1.24		.46
FAGU158	14091	53.2	56.0	2.8	4L42		.14	.19	.16	7.0					.35		.46
FAGU158	14092	68.6	69.6	1.0	4L67		.07	.76	.67	15.0					1.43		.47
FAGU174	14094	18.3	19.9	1.6	94 4DA		.05	3.27	5.30	51.0					8.57		.62
FAGU174	14095	27.2	27.7	.5	100 4D54		.03	4.16	8.90	75.0					13.06		.68
FAGU174	14096	27.7	28.0	.3	100 4E0		.41	1.29	1.10	43.0					2.39		.46
FAGU164	14097	.0	3.7	3.7	32 4A4	3.52	.24	2.87	4.16	55.0	1.03	.96	17.20		7.03	18.16	.59
FAGU164	14098	3.7	6.3	2.6	58 4E4	4.27	.09	8.33	11.80	141.0	1.23	1.92	21.40		20.13	23.32	.59
FAGU164	14099	6.3	7.8	1.5	100 4A4	3.30	.07	2.67	5.10	45.0	.34	2.13	10.60		7.77	12.73	.66
FAGU164	14100	8.4	10.7	2.3	83 4A4	3.24	.06	3.78	4.91	68.0	.89	1.05	10.40		8.69	11.45	.57
FAGU164	14101	10.7	11.7	1.0	100 4ADE	4.03	.09	8.00	15.50	155.0	.89	2.97	16.50		23.50	19.47	.66
FAGU164	14102	11.7	12.0	.3	100 4G4	4.45	.15	4.91	10.80	112.0	2.19	1.65	22.10		15.71	23.75	.69
FAGU164	14103	42.7	43.7	1.0	100 4GE		.09	7.10	6.60	114.0					13.70		.48
FAGU188	14104	2.9	4.7	1.8	94 4C5		.06	1.02	1.79	18.0					2.81		.64
FAGU188	14105	4.7	6.5	1.8	83 4C5		.08	.35	2.15	14.0					3.00		.72
FAGU188	14106	6.5	8.1	1.6	100 4C5		.04	.67	2.06	11.0					2.73		.75
FAGU188	14107	8.1	10.1	2.0	100 4L12		.05	.49	.71	10.0					1.20		.59
FAGU188	14108	10.1	12.1	2.0	95 4L12		.05	.24	.35	6.0					.59		.59
FAGU188	14109	12.1	13.9	1.8	100 4L12		.06	.24	.38	8.0					.62		.61
FAGU188	14110	13.9	15.5	1.6	100 4C5		.06	.73	1.68	13.0					2.41		.70
FAGU188	14111	15.5	17.3	1.8	78 4D5	2.96	.02	1.91	3.57	34.0	.14	1.15	3.23		5.48	4.38	.65
FAGU188	14112	17.3	19.3	2.0	100 4L12	2.98	.04	2.44	4.42	40.0	.21	1.20	3.38		6.86	4.58	.64
FAGU188	14113	19.3	21.5	2.2	91 4L12	3.00	.02	2.83	5.20	47.0	.48	1.50	2.20		8.03	3.70	.65
FAGU188	14114	21.9	22.8	.9	78 4L12	2.95	.01	1.47	3.62	27.0	.34	1.38	1.53		5.09	2.91	.71
FAGU188	14115	22.8	24.8	2.0	100 4A4	3.08	.04	2.60	4.70	42.0	.69	1.24	5.10		7.30	6.34	.64
FAGU188	14116	24.8	26.8	2.0	95 4A0		.08	.29	.62	7.0					.91		.68
FAGU188	14117	26.8	28.8	2.0	100 4A0		.06	.69	1.11	14.0					1.80		.62
FAGU188	14118	28.8	30.8	2.0	100 4A0		.08	.37	.69	10.0					1.06		.65
FAGU188	14119	30.8	33.1	2.3	100 4A0		.12	.48	1.04	15.0					1.52		.68
FAGU188	14120	33.1	34.5	1.4	100 4L12		.06	.47	.99	20.0					1.46		.68
FAGU188	14121	34.5	37.2	2.7	100 4C5		.08	.53	1.68	18.0					2.21		.76
FAGU188	14122	37.7	40.7	3.0	93 4C5		.03	.52	1.11	11.0					1.63		.68
FAGU188	14123	42.9	44.9	2.0	100 4A4		.02	1.84	4.10	36.0					5.94		.69
FAGU188	14124	55.9	57.9	2.0	100 3G16		.05	.69	1.00	14.0					1.69		.59
FAGU190	14125	31.2	33.3	2.1	100 4A0	3.00	.03	1.01	.47	19.0	.62	1.07	6.80		1.48	7.87	.32
FAGU190	14126	33.3	34.9	1.6	100 4C5	2.90	.02	1.05	1.71	17.0	.21	1.34	1.81		2.76	3.15	.62
FAGU190	14127	34.9	36.5	1.6	94 4C5	2.91	.05	.88	1.88	16.0	.21	1.57	1.79		2.76	3.36	.68
FAGU190	14128	36.5	38.4	1.9	89 5D4*		.04	.15	.19	6.0					.34		.56
FAGU190	14129	38.4	40.4	2.0	90 4C0		.04	.30	.70	8.0					1.00		.70
FAGU190	14130	40.4	42.4	2.0	95 4C0		.05	.30	1.07	9.0					1.37		.78
FAGU190	14131	42.4	44.4	2.0	95 4C0		.04	.43	.52	10.0					.95		.55
FAGU190	14132	44.4	45.2	.8	75 4D0	3.14	.12	1.82	4.06	35.0	.34	1.28	7.60		5.88	8.88	.69
FAGU190	14133	45.2	47.2	2.0	100 4A0	3.31	.10	1.45	3.46	31.0	1.30	1.26	13.80		4.91	15.06	.70
FAGU190	14134	47.2	48.7	1.5	100 4A4	3.29	.06	4.26	8.50	63.0	.89	1.17	9.50		12.76	10.67	.67
FAGU190	14135	48.7	50.7	2.0	100 4A30	3.69	.17	1.16	1.47	32.0	1.10	.97	22.00		2.63	22.97	.56



DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	FY	BAO	PB+ZN	PC+PY	ZN		
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	%	RATIO	
FAGU160	14186	65.3	65.6	.3	100	4G4		.08	5.50	7.60	110.0								13.10	.58
FAGU160	14187	67.1	69.2	2.1	90	4A4		.04	5.90	4.77	63.0								10.67	.45
FAGA051	14188	169.9	172.0	2.1	100	4L74		.10	1.02	1.21	17.0								2.23	.54
FAGA051	14189	172.0	173.8	1.8	94	4L74		.12	.78	.72	16.0								1.50	.48
FAGA051	1419C	173.8	174.8	1.0	90	4L0		.09	.45	.48	11.0								.93	.52
FAGA051	14191	203.9	205.7	1.8	100	4L74		.06	.57	.54	11.0								1.11	.49
FAGA051	14192	205.7	207.7	2.0	95	4L74		.09	.79	.69	15.0								1.48	.47
FAGA051	14193	207.7	209.1	1.4	100	4G0	4.48	.14	2.75	2.50	62.0	.75	2.00	31.50				5.25	33.50	.48
FAGA051	14194	209.1	210.4	1.3	100	4G4	4.64	.15	6.30	5.20	93.0	.69	3.90	22.50				11.50	26.40	.45
FAGA051	14195	210.4	212.3	1.9	95	4C7	3.39	.14	.61	1.39	15.0	.27	4.20	13.20				2.00	17.40	.69
FAGA051	14196	212.3	214.0	1.7	100	4C7	3.70	.17	1.85	2.79	29.0	.27	9.10	13.50				4.64	22.60	.60
FAGA051	14197	297.5	299.0	1.5	100	4L46	3.17	.05	.63	1.47	12.0	.27	5.20	4.85				2.10	10.05	.70
FAGA051	14198	299.0	300.5	1.5	100	4L46	3.47	.06	1.22	1.68	24.0	.48	4.58	12.80				2.90	17.38	.58
FAGA051	14199	300.5	302.1	1.6	94	4A0	3.65	.16	1.57	1.60	29.0	.69	3.61	15.60				3.17	19.21	.50
FAGA051	14200	302.1	303.3	1.2	100	4A0		.13	.49	.53	13.0								1.02	.52
FAGA051	14201	303.3	305.0	1.7	94	4C5		.14	.87	.65	18.0								1.52	.43
FAGA051	14202	307.8	309.7	1.9	95	4C5\$		.13	.45	.44	11.0								.89	.49
FAGA051	14203	309.7	311.2	1.5	100	4C5\$		.30	.25	.44	9.0								.69	.64
FAGA051	14204	311.2	312.8	1.6	94	4C5\$		.12	.54	.55	12.0								1.09	.50
FAGA051	14205	312.8	313.8	1.0	100	4C\$		.09	1.12	1.08	20.0								2.20	.49
FAGA051	14206	324.9	325.7	.8	100	4C\$#		.09	1.92	1.72	24.0								3.64	.47
FAGA051	14207	335.3	336.3	1.0	100	4C\$\$		.14	2.22	2.29	35.0								4.51	.51
FAGA051	14208	337.7	338.8	1.1	100	4G08		.14	1.74	1.65	29.0								3.39	.49
FAGA051	14209	340.2	341.5	1.3	92	4C\$		.14	1.26	1.36	22.0								2.62	.52
FAGA051	14210	341.5	343.2	1.7	100	4A\$		.18	.21	.32	8.0								.53	.60
FAGA051	14211	343.2	345.0	1.8	94	4C5\$		.11	.41	.55	9.0								.96	.57
FAGA051	14212	345.0	346.1	1.1	100	4G0\$	4.27	.18	3.17	4.84	43.0	.75	2.58	17.50				8.01	20.08	.60
FAGA051	14213	346.1	347.2	1.1	100	4C7\$	3.74	.21	1.56	2.00	26.0	.69	8.40	17.00				3.56	25.40	.56
FAGU170	14214	1.0	2.9	1.9	84	4A34	3.30	.04	2.14	3.72	46.0	.75	1.35	10.30				5.86	11.65	.63
FAGU170	14215	2.9	4.8	1.9	95	4A34	3.56	.03	3.92	7.30	70.0	.75	1.34	14.60				11.22	15.94	.65
FAGU170	14216	4.8	6.7	1.9	100	4A34	3.43	.05	2.10	3.40	50.0	.69	1.36	14.10				5.50	15.46	.62
FAGU170	14217	6.7	8.7	2.0	95	4A34	3.53	.06	2.80	5.60	59.0	.96	1.35	13.70				8.40	15.05	.67
FAGU170	14218	8.7	10.7	2.0	95	4C5	2.98	.02	.88	1.30	15.0	.75	1.11	2.04				2.18	3.15	.60
FAGU170	14219	10.7	12.7	2.0	100	4C5	3.02	.03	1.76	2.44	29.0	.55	.89	1.48				4.20	2.37	.58
FAGU170	14220	12.7	14.7	2.0	85	4D5	3.07	.02	3.39	3.27	80.0	.69	.87	2.16				6.66	3.03	.49
FAGU170	14221	14.7	16.7	2.0	75	4D5	3.10	.02	1.83	4.11	36.0	.34	1.09	2.05				5.94	3.14	.69
FAGU170	14222	16.7	18.7	2.0	90	4D5	3.08	.02	3.52	3.66	94.0	.34	1.13	1.48				7.18	2.61	.51
FAGU170	14223	18.7	20.7	2.0	75	4C5	3.06	.02	.91	3.06	19.0	.21	1.68	.68				3.97	2.36	.77
FAGU170	14224	20.7	23.0	2.3	87	4C5		.01	.46	1.31	9.0							1.77		.74
FAGU170	14225	23.0	25.1	2.1	90	4C5		.03	.30	.83	7.0							1.13		.74
FAGU170	14226	25.1	27.5	2.4	83	4C5	3.01	.02	1.44	2.31	24.0	.27	.91	2.10				3.75	3.01	.62
FAGU170	14227	27.5	29.2	1.7	82	4C5	3.03	.03	.79	1.27	16.0	.14	2.21	1.68				2.06	3.89	.62
FAGU170	14228	30.4	32.8	2.4	17	4A0	3.53	.04	1.41	3.56	29.0	.48	2.06	12.00				4.97	14.06	.72
FAGU170	14229	32.8	34.0	1.2	50	4KEA	3.36	.05	4.01	8.80	83.0	.41	1.24	8.10				12.81	9.34	.69
FAGU170	14230	34.0	35.9	1.9	53	4KE	3.88	.06	6.80	12.40	120.0	.34	1.58	15.60				19.20	17.18	.65
FAGU170	14231	37.0	37.9	.9	100	4D\$4	3.98	.06	3.95	9.10	75.0	.41	2.02	18.20				13.05	20.22	.70
FAGU170	14232	37.9	40.7	2.8	89	4A34	3.31	.04	4.98	5.70	81.0	.69	1.12	9.60				10.68	10.72	.53
FAGU170	14233	40.7	43.0	2.3	70	4K4	3.53	.05	3.35	7.50	59.0	.55	2.23	3.40				10.85	5.63	.69
FAGU170	14234	43.0	45.7	2.7	85	4K4	3.73	.01	2.22	4.32	46.0	.41	1.58	19.50				6.54	21.08	.66
FAGU170	14235	45.7	46.7	1.0	90	4E4	3.97	.14	6.30	9.60	134.0	1.44	.89	20.00				15.90	20.89	.60

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAG	PB+ZN	PC+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGU170	14236	46.7	48.7	2.0	85	4A4	3.36	.06	4.82	7.00	80.0	.96	1.15	10.10		11.82	11.25	.59
FAGU170	14237	48.7	50.3	1.6	62	4AE	3.39	.06	1.94	3.10	40.0	1.23	2.69	11.80		5.04	14.49	.62
FAGU170	14238	50.3	52.5	2.2	91	4A34	3.32	.05	4.80	6.50	73.0	.89	.93	10.70		11.30	11.63	.58
FAGU170	14239	52.5	54.8	2.3	87	4A34	3.40	.06	3.31	3.91	52.0	1.17	4.08	12.50		7.22	16.58	.54
FAGAO12	14240	205.4	207.4	2.0	95	4A4		.06	2.77	5.70	49.0					8.47		.67
FAGAO12	14241	207.4	209.3	1.9	95	5D4*		.05	.55	.73	12.0					1.28		.57
FAGAO12	14242	209.3	211.1	1.8	89	4A0		.03	.28	.66	6.0					.94		.70
FAGAO12	14243	211.1	212.9	1.8	83	4A0		.04	.62	1.16	11.0					1.78		.65
FAGAO12	14244	212.9	214.3	1.4	93	4A0		.06	.78	.70	13.0					1.48		.47
FAGAO12	14245	214.3	216.1	1.8	100	4A0		.07	.20	.46	4.0					.66		.70
FAGAO12	14246	216.1	218.2	2.1	90	4C5		.07	.15	.49	4.0					.64		.77
FAGAO12	14247	218.2	219.7	1.5	87	5A19		.10	.40	.71	8.0					1.11		.64
FAGAO12	14248	219.7	221.7	2.0	95	4C0		.11	.41	.82	8.0					1.23		.67
FAGAO12	14249	221.7	222.6	.9	89	5D4*		.06	.27	.58	6.0					.85		.68
FAGAO12	14250	222.6	224.2	1.6	87	4C5		.10	.44	.70	8.0					1.14		.61
FAGAO12	14251	224.2	226.0	1.8	94	4C0		.10	.58	1.55	12.0					2.13		.73
FAGAO12	14252	226.0	227.5	1.5	87	4C5		.08	.43	.97	9.0					1.40		.69
FAGAO12	14253	227.5	228.9	1.4	79	4A0		.05	.44	.88	9.0					1.32		.67
FAGAO12	14254	228.9	230.1	1.2	75	4A4		.04	1.51	4.17	33.0					5.68		.73
FAGAO12	14255	256.3	257.9	1.6	87	4C5		.02	1.65	2.53	21.0					4.18		.61
FAGAO12	14256	257.9	259.7	1.8	94	4L27		.05	.37	.62	8.0					.99		.63
FAGAO12	14257	272.7	273.9	1.2	100	4C5	2.97	.07	1.20	1.68	21.0	.41	2.92	4.38		2.88	7.30	.58
FAGAO12	14258	273.9	276.5	2.6	96	4C0	2.90	.03	1.17	2.04	17.0	.89	1.65	1.85		3.21	3.50	.64
FAGAO12	14259	276.5	278.0	1.5	80	4L12		.03	.64	1.82	12.0					2.46		.74
FAGAO12	14260	278.0	279.5	1.5	93	4C5		.07	.61	1.91	15.0					2.52		.76
FAGAO12	14261	279.5	281.3	1.8	94	4A0	3.36	.11	1.41	2.72	30.0	.75	1.15	15.40		4.13	16.55	.66
FAGAO12	14262	281.3	283.3	2.0	90	4A4	3.26	.12	1.99	3.08	39.0	.89	.88	13.70		5.07	14.58	.61
FAGAO12	14263	283.3	284.4	1.1	91	4C0		.05	.42	.78	13.0					1.20		.65
FAGAO12	14264	284.4	286.4	2.0	95	4L12		.09	.43	.35	10.0					.78		.45
FAGAO12	14265	286.4	287.5	1.1	100	4L12		.05	.06	.17	3.0					.23		.75
FAGAO12	14266	287.5	289.1	1.6	94	4L12		.08	1.16	1.18	18.0					2.34		.50
FAGAO12	14267	289.1	290.5	1.4	93	4A0		.15	.56	.80	17.0					1.36		.59
FAGAO12	14268	290.5	292.2	1.7	88	4A0		.09	1.72	2.54	30.0					4.26		.60
FAGAO12	14269	292.2	294.0	1.8	94	4A13		.19	.51	.42	25.0					.93		.45
FAGAO12	14270	294.0	296.1	2.1	95	4A13		.19	.63	.37	24.0					1.00		.37
FAGAO12	14271	296.1	298.4	2.3	96	4A0	3.14	.09	1.19	1.19	25.0	1.33	.61	9.90		2.38	10.51	.50
FAGAO12	14272	298.4	300.4	2.0	95	4A0	3.19	.10	1.30	2.21	27.0	1.23	1.38	11.90		3.51	13.28	.63
FAGAO12	14273	300.4	302.4	2.0	95	4L12		.05	.39	.27	8.0					.66		.41
FAGAO12	14274	302.4	304.5	2.1	95	4A0		.13	.85	1.15	18.0					2.00		.58
FAGAO12	14275	304.5	306.2	1.7	94	4A0		.09	.99	1.06	17.0					2.05		.52
FAGAO12	14276	306.2	308.0	1.8	100	4A13		.14	1.78	.41	41.0					2.19		.19
FAGAO12	14277	308.0	309.8	1.8	94	4A13		.14	1.00	.18	26.0					1.18		.15
FAGAO12	14278	309.8	311.7	1.9	89	4A13		.09	.94	.67	25.0					1.61		.42
FAGAO12	14279	311.7	313.5	1.8	100	4A13		.15	.34	.30	20.0					.64		.47
FAGAO12	14280	313.5	315.3	1.8	89	4A13		.18	.07	.31	16.0					.38		.82
FAGAO12	14281	315.3	317.1	1.8	94	4A13		.12	.12	.23	12.0					.35		.66
FAGAO12	14282	317.1	318.4	1.3	92	4A13		.16	.04	.23	12.0					.27		.85
FAGAO12	14283	318.4	319.9	1.5	80	4G4	4.64	.24	4.95	7.90	102.0	.21	.87	28.40		12.85	29.27	.61
FAGAO12	14284	319.9	321.3	1.4	71	4G4	4.47	.18	3.80	5.50	70.0	.48	1.18	29.70		9.30	30.88	.59
FAGU180	14285	.0	2.1	2.1	19	4A41	3.64	.07	6.00	10.70	91.0	1.03	9.20	3.70		16.70	12.90	.64



DDH	SAMPLE	---DEPTHS---	INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAC	PB+ZN	PO+PY	ZN
		FROM TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGU186	14336	3.8 5.8	2.0	85	4A0		.06	1.44	1.74	25.0					3.18		.55
FAGU186	14337	5.8 7.8	2.0	95	4A0		.06	.50	1.14	12.0					1.64		.70
FAGU186	14338	7.8 9.8	2.0	85	4A0		.06	.63	1.38	14.0					2.01		.69
FAGU186	14339	10.8 11.6	.8	87	4DE		.07	2.12	4.22	41.0					6.34		.67
FAGU176	14340	27.9 29.5	1.6	88	4A4	3.16	.01	3.89	8.30	74.0	.48	1.72	5.90		12.19	7.62	.68
FAGU176	14341	29.5 30.9	1.4	79	4A4	3.21	.06	3.20	7.40	78.0	.82	1.78	5.20		10.60	6.98	.70
FAGU176	14342	58.6 61.1	2.5	68	4A34	3.50	.05	4.77	8.40	77.0	.96	1.55	12.30		13.17	13.85	.64
FAGU176	14343	61.1 62.8	1.7	88	4E4	3.83	.08	1.74	3.42	39.0	1.37	1.66	21.70		5.16	23.36	.66
FAGU176	14344	110.0 111.6	1.6	94	4AL		.07	.59	.85	16.0					1.44		.59
FAGU176	14345	111.6 113.2	1.6	100	4A0		.08	.87	.99	20.0					1.86		.53
FAGU176	14346	113.2 115.7	2.5	100	4A31		.14	.70	.62	24.0					1.32		.47
FAGU176	14347	115.7 117.3	1.6	87	4E46		.17	5.00	8.00	77.0					13.00		.62
FAGU176	14348	150.8 152.7	1.9	95	4E46	4.55	.09	4.44	7.20	78.0	1.03	1.12	22.80		11.64	23.92	.62
FAGU176	14349	152.7 154.6	1.9	100	4E46	5.02	.36	6.40	9.50	119.0	.82	.89	25.70		15.90	26.59	.60
FAGU176	14350	154.6 157.0	2.4	92	4E4	4.67	.29	3.10	3.85	50.0	.96	.84	36.10		6.95	36.94	.55
FAGU176	14351	157.0 159.5	2.5	96	4E0	4.54	.30	1.82	3.09	38.0	.89	.95	34.30		4.91	35.25	.63
FAGU176	14352	159.5 162.0	2.5	100	4A34	3.57	.08	4.28	8.30	75.0	1.44	1.04	14.70		12.58	15.74	.66
FAGU184	14353	.0 2.7	2.7	26	4A0		.09	.78	1.45	17.0					2.23		.65
FAGU184	14354	3.2 5.0	1.8	100	4CA		.14	.58	1.72	13.0					2.30		.75
FAGU184	14355	5.8 7.8	2.0	100	4CA		.14	.61	.70	12.0					1.31		.53
FAGU184	14356	7.8 9.8	2.0	100	4CA		.08	.71	1.46	15.0					2.17		.67
FAGU184	14357	9.8 11.8	2.0	100	4CA		.05	.73	1.31	15.0					2.04		.64
FAGU184	14358	11.8 13.8	2.0	100	4ACD	3.16	.05	3.43	6.80	58.0	.48	1.69	5.70		10.23	7.39	.66
FAGU184	14359	23.2 24.7	1.5	60	4A4		.07	2.52	4.38	38.0					6.90		.63
FAGU184	14360	26.3 27.9	1.6	81	4C0	2.97	.07	1.77	2.44	28.0	.48	2.42	3.71		4.21	6.13	.58
FAGU184	14361	27.9 29.3	1.4	93	4A0	3.01	.05	1.31	2.64	22.0	.48	1.90	4.71		3.95	6.61	.67
FAGU184	14362	29.3 31.3	2.0	95	4C5		.05	.56	1.08	11.0					1.64		.66
FAGU184	14363	31.3 33.3	2.0	100	4C5		.06	.71	.96	15.0					1.67		.57
FAGU184	14364	33.3 35.8	2.5	96	4C0		.05	.44	1.22	10.0					1.66		.73
FAGU184	14365	35.8 37.6	1.8	100	4A0		.07	.67	1.09	13.0					1.76		.62
FAGU184	14366	37.6 39.6	2.0	90	4C0		.04	.82	1.42	15.0					2.24		.63
FAGU184	14367	39.6 41.6	2.0	90	4C0		.03	.56	.83	11.0					1.39		.60
FAGU184	14368	41.6 42.7	1.1	82	4C0		.05	.70	1.08	14.0					1.78		.61
FAGU184	14369	42.7 44.7	2.0	100	4C5		.06	.68	1.42	14.0					2.10		.68
FAGU184	14370	44.7 46.7	2.0	90	4C5		.05	.50	1.05	10.0					1.55		.68
FAGU184	14371	46.7 49.0	2.3	87	4C5		.05	.81	1.04	19.0					1.85		.56
FAGU184	14372	50.5 51.8	1.3	54	4C0		.11	.43	.36	19.0					.79		.46
FAGU184	14373	51.8 53.8	2.0	100	4A4	3.39	.06	6.35	8.80	95.0	.96	1.51	8.90		15.15	10.41	.58
FAGU184	14374	53.8 55.8	2.0	100	4A4	3.53	.08	4.30	10.50	73.0	.89	7.86	1.65		14.80	9.51	.71
FAGU184	14375	55.8 57.9	2.1	86	4A4	3.42	.16	4.56	9.60	75.0	1.17	1.33	11.60		14.16	12.93	.68
FAGU184	14376	57.9 59.2	1.3	100	4E4	4.40	.13	5.00	5.50	80.0	1.03	1.77	29.50		10.50	31.27	.52
FAGU184	14377	64.3 66.1	1.8	100	4E44	4.50	.12	7.20	14.30	125.0	.82	1.34	22.80		21.50	24.14	.67
FAGU184	14378	66.1 67.8	1.7	94	4E44	4.05	.06	11.00	16.40	148.0	1.37	2.22	13.60		27.40	15.82	.60
FAGU184	14379	68.6 70.9	2.3	65	4E4	3.60	.08	7.10	9.80	104.0	1.37	4.67	10.20		16.90	14.87	.58
FAGU184	14380	98.0 100.6	2.6	100	4ALC	3.15	.12	1.67	2.44	29.0	1.58	6.45	5.80		4.11	12.25	.59
FAGU184	14381	107.8 109.0	1.2	100	4A7		.08	1.85	2.37	28.0					4.22		.56
FAGU184	14382	109.0 110.7	1.7	88	4C5		.16	.75	.94	13.0					1.69		.56
FAGU184	14383	110.7 111.9	1.2	100	4C57		.29	.83	1.02	18.0					1.85		.55
FAGU184	14384	111.9 113.4	1.5	100	4E68	4.14	.25	2.60	4.08	48.0	.82	4.48	23.90		6.68	28.38	.61
FAGU184	14385	113.4 114.5	1.1	100	4C5	3.47	.47	1.37	1.65	28.0	.89	10.00	12.60		3.02	22.60	.55

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAO	PB+ZN	PC+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGU184	14386	114.5	117.1	2.6	96	4AC		.16	.28	.20	4.0					.48		.42
FAGU184	14387	117.1	118.2	1.1	100	4C5		.17	.66	.95	12.0					1.61		.59
FAGU184	14388	118.2	119.3	1.1	100	4ACD		.08	1.69	3.18	30.0					4.87		.65
FAGU184	14389	122.4	124.4	2.0	95	4E48	3.74	.17	1.30	1.75	23.0	.96	5.46	20.00		3.05	25.46	.57
FAGU184	1439C	124.4	126.4	2.0	100	4CE8	3.77	.22	1.76	2.18	29.0	.62	5.44	21.10		3.94	26.54	.55
FAGU184	14391	126.4	128.2	1.8	100	4C58		.14	.52	.69	11.0					1.21		.57
FAGU184	14392	128.2	130.7	2.5	96	4A0		.16	.10	.17	9.0					.27		.63
FAGU184	14393	130.7	132.7	2.0	100	4C0		.15	.15	.12	10.0					.27		.44
FAGU184	14394	132.7	134.0	1.3	100	4A0		.26	.10	.20	10.0					.30		.67
FAGU184	14395	134.0	136.6	2.6	100	4C7		.18	.70	1.04	17.0					1.74		.60
FAGU184	14396	136.6	137.7	1.1	100	4EG8	4.58	.16	4.07	5.40	57.0	.82	2.36	23.20		9.47	25.56	.57
FAGU184	14397	137.7	140.0	2.3	100	4C0		.20	.42	.72	13.0					1.14		.63
FAGU184	14398	140.0	141.8	1.8	100	4GE4	4.26	.19	4.34	5.70	59.0	.75	2.30	18.40		10.04	20.70	.57
FAGU184	14399	141.8	143.5	1.7	100	4GE4	4.64	.30	5.70	7.30	82.0	1.37	.83	19.90		13.00	20.73	.56
FAGU184	14400	143.5	146.5	3.0	100	4A0	3.12	.03	.98	1.67	20.0	.27	3.22	8.20		2.65	11.42	.63
FAGU182	14401	.0	3.3	3.3	39	4A0		.13	.46	1.09	9.0					1.55		.70
FAGU182	14402	3.3	5.4	2.1	71	4C0		.10	.55	.75	11.0					1.30		.58
FAGU182	14403	5.4	6.5	1.1	100	4D5	3.12	.03	4.16	4.81	76.0	.62	2.76	4.73		8.97	7.49	.54
FAGU182	14404	6.5	8.6	2.1	86	4A0	3.02	.02	1.79	3.34	31.0	.34	.77	2.63		5.13	3.40	.65
FAGU182	14405	8.6	10.7	2.1	57	4A34	3.76	.02	3.19	6.59	54.0	.69	1.83	20.40		9.78	22.23	.67
FAGU182	14406	15.4	20.5	5.1	41	4A0		.06	.65	1.56	13.0					2.21		.71
FAGU182	14407	20.5	22.5	2.0	40	4A0		.09	.51	1.20	11.0					1.71		.70
FAGU182	14408	22.5	25.0	2.5	60	4C0		.04	1.01	2.21	16.0					3.22		.69
FAGU182	14409	51.8	53.5	1.7	82	4A1	3.36	.07	1.67	2.62	34.0	.69	1.84	14.50		4.29	16.34	.61
FAGU182	14410	53.5	55.1	1.6	63	4C0	3.06	.05	1.08	1.65	24.0	.41	2.96	4.84		2.73	7.80	.60
FAGU182	14411	55.1	56.2	1.1	100	4G4	4.35	.08	5.30	11.10	120.0	1.03	.90	11.20		16.40	12.10	.68
FAGU182	14412	59.4	61.2	1.8	94	4G4	4.54	.04	4.69	9.13	95.0	.62	.66	17.20		13.82	17.86	.66
FAGU182	14413	62.0	63.6	1.6	100	4G4	4.68	.17	6.90	13.90	119.0	1.85	.87	21.40		20.80	22.27	.67
FAGU182	14414	63.6	65.1	1.5	100	4G4	4.70	.24	6.60	12.70	113.0	2.13	.63	16.10		19.30	16.73	.66
FAGU182	14415	65.1	66.9	1.8	100	4E46	4.67	.20	4.83	8.20	104.0	1.44	1.00	26.40		13.03	27.40	.63
FAGU182	14416	66.9	68.9	2.0	100	4E46	4.86	.26	4.47	5.60	80.0	1.23	.71	32.60		10.07	33.31	.56
FAGU182	14417	68.9	70.8	1.9	100	4E44	4.62	.14	7.30	13.00	116.0	1.30	1.34	22.20		20.30	23.54	.64
FAGU182	14418	142.6	143.8	1.2	100	4G4		.10	5.20	8.30	91.0					13.50		.61
FAGAO12	14419	354.5	356.3	1.8	61	4E4	4.73	.19	4.19	5.60	60.0	1.17	.99	32.60		9.79	33.59	.57
FAGAO12	14420	356.3	358.4	2.1	100	4E4	4.90	.23	4.38	4.49	69.0	1.17	.98	36.30		8.87	37.28	.51
FAGAO12	14421	358.4	359.8	1.4	100	4G4	4.62	.08	4.51	8.50	79.0	1.17	.65	17.00		13.01	17.65	.65
FAGAO12	14422	359.8	361.2	1.4	79	4EG	4.05	.04	1.88	4.02	41.0	.82	1.46	23.80		5.90	25.26	.68
FAGAO12	14423	361.2	362.6	1.4	93	4EG	4.67	.12	1.90	6.20	54.0	1.65	19.73	.77		8.10	20.50	.77
FAGAO12	14424	362.6	363.2	.6	100	4G4	4.50	.12	3.40	9.10	65.0	1.23	.73	11.60		12.50	12.33	.73
FAGAO12	14425	363.2	364.5	1.3	85	4E0	4.55	.20	1.85	1.45	33.0	1.10	1.52	34.40		3.30	35.92	.44
FAGA113	14426	215.4	217.2	1.8	94	4D4	3.39	.08	4.65	10.50	92.0	.69	4.91	7.60		15.15	12.51	.69
FAGA113	14427	217.2	219.6	2.4	100	4A0	3.02	.06	1.03	2.00	24.0	.41	2.13	5.80		3.03	7.93	.66
FAGA113	14428	219.6	221.6	2.0	95	4A0	2.97	.06	.90	1.78	19.0	.27	1.62	3.98		2.68	5.60	.66
FAGA113	14429	221.6	223.6	2.0	100	4A0	3.00	.07	.47	.71	10.0	.41	1.54	6.10		1.18	7.64	.60
FAGA113	14430	223.6	225.6	2.0	100	4A0	3.01	.07	.76	1.02	15.0	.55	1.62	5.20		1.78	6.82	.57
FAGA113	14431	225.6	226.7	1.1	100	4A4	3.58	.04	4.55	7.80	83.0	.82	2.26	14.70		12.35	16.96	.63
FAGA113	14432	310.3	312.4	2.1	81	4C5	2.94	.06	1.12	1.04	20.0	.27	1.63	3.87		2.16	5.50	.48
FAGA113	14433	312.4	314.0	1.6	100	4D0	2.91	.04	1.86	3.29	29.0	.21	1.22	1.18		5.15	2.40	.64
FAGA113	14434	314.0	315.1	1.1	100	4C0	2.94	.04	.95	2.26	18.0	.34	1.68	2.12		3.21	3.80	.70
FAGA113	14435	316.2	318.6	2.4	100	4D0	3.13	.13	2.66	4.59	48.0	.48	1.69	8.30		7.25	9.99	.63

DDH	SAMPLE	---DEPTHS---	INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAO	PB+ZN	PC+PY	ZN
		FROM TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGA113	14436	318.6	319.5	.9	100	5D4*	.09	.30	.45	9.0					.75		.60
FAGA113	14437	319.5	321.3	1.8	56	4A0	.07	.32	.79	11.0					1.11		.71
FAGA113	14438	325.3	327.6	2.3	57	4C0	.06	.29	.25	9.0					.54		.46
FAGA113	14439	329.2	331.0	1.8	39	4D5	4.35	.08	3.32	6.30	62.0	.96	5.07	18.50	9.62	23.57	.65
FAGA113	14440	365.1	368.5	3.4	85	4GHEL	.15	.37	.87	15.0					1.24		.70
FAGA113	14441	368.5	370.9	2.4	87	4G4	4.61	.10	4.06	8.00	81.0	.82	.64	16.00	12.06	16.64	.66
FAGA113	14442	370.9	373.5	2.6	100	5C*9	3.20	.01	1.04	2.29	18.0	.14	5.90	4.00	3.33	9.90	.69
FAGA113	14443	373.5	375.4	1.9	100	4G4	4.39	.13	4.84	8.60	92.0	1.17	.77	21.20	13.44	21.97	.64
FAGA113	14444	375.4	376.6	1.2	100	4A14	3.39	.04	2.40	5.90	46.0	.96	1.36	14.60	8.30	15.96	.71
FAGA113	14445	376.6	377.9	1.3	100	4E46	3.95	.07	3.98	7.60	82.0	1.03	.96	14.50	11.58	15.46	.66
FAGA113	14446	377.9	380.2	2.3	91	4E46	3.58	.08	2.13	3.13	43.0	.69	4.69	15.60	5.26	20.29	.60
FAGA113	14447	403.6	405.2	1.6	100	4A17		.08	.26	.32	8.0				.58		.55
FAGA113	14448	406.1	407.3	1.2	100	4A1		.06	.29	.21	7.0				.50		.42
FAGA113	14449	420.2	422.5	2.3	100	4A1		.06	.46	.96	11.0				1.42		.68
FAGA113	14450	428.5	430.5	2.0	100	4A7		.09	.84	.08	10.0				.92		.09
FAGA113	14451	430.5	432.4	1.9	100	4A7		.13	.12	.10	10.0				.22		.46
FAGA154	14452	72.5	74.3	1.8	100	4CL		.01	.83	1.22	12.0				2.05		.60
FAGA154	14453	74.3	76.1	1.8	94	4CL		.02	2.22	1.85	28.0				4.07		.45
FAGA154	14454	127.4	128.6	1.2	58	4AE		.02	.97	1.95	21.0				2.92		.67
FAGA154	14455	130.1	132.0	1.9	74	4E\$		.02	1.21	2.46	23.0				3.67		.67
FAGA154	14456	132.0	133.8	1.8	89	4A4		.01	2.00	3.36	39.0				5.36		.63
FAGA154	14457	134.9	135.6	.7	100	4EF4		.02	4.85	14.50	92.0				19.35		.75
FAGA154	14458	136.8	139.6	2.8	82	4A4		.02	2.41	4.68	47.0				7.09		.66
FAGA114	14459	93.3	94.8	1.5	100	4C3\$		.27	.49	.24	20.0				.73		.33
FAGA114	14460	94.8	96.3	1.5	100	4C3\$		.26	1.33	.86	27.0				2.19		.39
FAGA114	14461	96.3	97.8	1.5	100	4C3\$		.23	.97	.83	19.0				1.80		.46
FAGA114	14462	97.8	100.7	2.9	69	4C3\$		.32	1.28	1.09	26.0				2.37		.46
FAGA114	14463	100.7	102.7	2.0	100	4C3\$		.24	1.34	1.32	26.0				2.66		.50
FAGA114	14464	102.7	104.7	2.0	100	4C3\$		.23	.84	.34	20.0				1.18		.29
FAGA114	14465	104.7	106.7	2.0	100	4C3\$		.21	.95	.61	27.0				1.56		.39
FAGA114	14466	106.7	108.5	1.8	100	4C3\$		.22	.99	.88	21.0				1.87		.47
FAGA114	14467	112.5	114.0	1.5	100	4C7		.28	1.26	1.36	23.0				2.64		.52
FAGA114	14468	114.0	115.4	1.4	100	4C7		.27	1.99	1.13	32.0				3.12		.36
FAGA114	14469	115.4	116.2	.8	100	4L27		.10	.36	.35	7.0				.71		.49
FAGA114	14470	116.2	117.8	1.6	100	4CL7		.21	.89	.80	17.0				1.69		.47
FAGA114	14471	117.8	120.5	2.7	100	4C79		.30	1.59	1.72	28.0				3.31		.52
FAGA114	14472	120.5	122.5	2.0	100	4CL7		.26	1.51	1.12	26.0				2.63		.43
FAGA114	14473	122.5	124.6	2.1	100	4C7		.33	1.42	1.20	26.0				2.62		.46
FAGA114	14474	127.0	128.8	1.8	100	4C7		.50	.84	.60	23.0				1.44		.42
FAGA114	14475	128.8	130.6	1.8	100	4E0		.37	.86	.60	23.0				1.46		.41
FAGA114	14476	130.6	132.3	1.7	100	4E0		.34	.92	.51	23.0				1.43		.36
FAGA114	14477	132.3	133.7	1.4	100	4C*		.19	1.19	.76	24.0				1.95		.39
FAGA114	14478	133.7	135.2	1.5	100	4D*		.21	2.46	2.58	42.0				5.04		.51
FAGA114	14479	135.2	137.2	2.0	100	4E46		.19	2.77	3.32	44.0				6.09		.55
FAGA114	14480	137.2	139.8	2.6	100	4ECL		.11	.54	.38	11.0				.92		.41
FAGA114	14481	139.8	141.9	2.1	86	4GEL		.07	3.49	3.67	43.0				7.16		.51
FAGA114	14482	141.9	144.0	2.1	95	4A31		.27	.70	1.35	21.0				2.05		.66
FAGA114	14483	144.0	146.4	2.4	46	4A31		.15	2.01	2.79	41.0				4.80		.58
FAGA114	14484	146.4	148.0	1.6	100	4EC\$		.23	1.26	1.42	25.0				2.68		.53
FAGA114	14485	148.0	149.8	1.8	89	4C8\$		.31	1.10	.75	25.0				1.85		.41

DDH	SAMPLE	---DEPTHS---	INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PC	PY	BAO	PB+ZN	PC+PY	ZN
		FROM	TO	M	%	UNIT	%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGA115	14486	221.3	223.1	1.8	100	4C*	.10	.81	.60	18.0					1.41		.43
FAGA115	14487	223.1	225.0	1.9	100	4C8*	.23	1.50	.99	30.0					2.49		.40
FAGA115	14488	225.0	225.8	.8	88	4G4	.12	5.70	7.60	132.0					13.30		.57
FAGA115	14489	327.0	328.3	1.3	92	4C0	.08	.68	1.17	16.0					1.85		.63
FAGA115	14490	328.3	331.4	3.1	97	5A19	.08	1.04	.66	21.0					1.70		.39
FAGA115	14491	331.4	332.5	1.1	100	4A0	.15	.61	.48	17.0					1.09		.44
FAGA115	14492	332.5	334.0	1.5	100	4DE	3.62	.19	2.71	3.39	53.0	.62	4.70	17.50	6.10	22.20	.56
FAGA115	14493	334.0	336.0	2.0	90	4A0	3.27	.21	.19	.34	11.0	.69	3.50	14.30	.53	17.80	.64
FAGA115	14494	336.0	338.0	2.0	100	4A0	3.35	.21	1.43	2.04	28.0	.82	3.69	13.40	3.47	17.09	.59
FAGA115	14495	338.0	340.0	2.0	100	4A0	.19	.17	.17	9.0					.34		.50
FAGA115	14496	340.0	342.0	2.0	100	4A0	.16	.15	.19	8.0					.34		.56
FAGA115	14497	342.0	343.5	1.5	100	4A0	.17	.37	.24	14.0					.61		.39
FAGA115	14498	343.5	345.5	2.0	100	4C*	.15	.15	.58	13.0					.73		.80
FAGA115	14499	345.5	347.5	2.0	100	4A1	.12	.27	.19	9.0					.46		.41
FAGA115	14500	347.5	349.8	2.3	100	4A1	.24	.35	.29	13.0					.64		.45
FAGA115	14501	349.8	350.6	.8	100	4E14	.47	3.71	4.53	66.0					8.24		.55
FAGA115	14502	350.6	352.2	1.6	94	4CA	.19	.50	.92	13.0					1.42		.65
FAGA115	14503	352.2	353.8	1.6	100	4A1	.15	.26	.39	7.0					.65		.60
FAGA115	14504	353.8	355.2	1.4	100	4C0	3.29	.22	1.06	1.00	17.0	.69	8.30	10.50	2.06	18.80	.49
FAGA115	14505	355.2	356.2	1.0	100	4G4	4.47	.19	4.19	6.10	53.0	.96	1.76	17.50	10.29	19.26	.59
FAGA115	14506	356.2	358.0	1.8	100	4A14	3.14	.05	2.01	3.62	29.0	.34	5.41	6.00	5.63	11.41	.64
FAGA115	14507	358.0	360.5	2.5	100	5D4*	.02	.18	.32	3.0					.50		.64
FAGA115	14508	360.5	361.4	.9	89	4A14	.08	2.03	5.27	26.0					7.30		.72
FAGA115	14509	408.6	410.2	1.6	87	4A1	.05	1.30	2.54	19.0					3.84		.66
FAGA115	14510	411.7	413.4	1.7	100	4L72	.07	2.50	.80	22.0					3.30		.24
FAGA115	14511	420.0	421.9	1.9	95	4EK16	4.35	.16	1.76	2.31	27.0	.69	5.75	27.60	4.07	33.35	.57
FAGA115	14512	421.9	423.5	1.6	94	4G4	4.51	.18	4.86	7.12	56.0	.75	1.74	17.40	11.98	19.14	.59
FAGA115	14513	423.5	425.2	1.7	100	4G4	4.62	.12	3.65	6.83	44.0	.82	1.23	17.10	10.48	18.33	.65
FAGA115	14514	425.2	426.8	1.6	100	4C8	3.57	.22	1.04	1.28	20.0	.75	5.55	16.60	2.32	22.15	.55
FAGA115	14515	426.8	428.3	1.5	80	4C8	3.72	.23	2.05	2.19	34.0	.82	6.70	19.20	4.24	25.90	.52
FAGA115	14516	428.3	430.4	2.1	90	4A17	.15	.53	.95	14.0					1.48		.64
FAGA115	14517	430.4	432.1	1.7	100	4EK1	.11	.70	1.00	21.0					1.70		.59
FAGA115	14518	432.1	433.2	1.1	100	4L24	.06	1.33	1.24	21.0					2.57		.48
FAGA111	14519	185.1	186.1	1.0	100	4C0	3.54	.21	1.76	1.31	29.0	.48	9.40	13.60	3.07	23.00	.43
FAGA111	14520	187.7	189.2	1.5	100	4C0	3.38	.17	1.43	1.57	21.0	.48	8.20	10.30	3.00	18.50	.52
FAGA111	14521	234.2	236.7	2.5	92	4E4	4.25	.11	6.44	18.60	117.0	1.10	3.30	17.10	25.04	20.40	.74
FAGA111	14522	237.9	239.0	1.1	100	4CE4	3.73	.09	2.36	4.66	73.0	.82	6.80	15.80	7.02	22.60	.66
FAGA111	14523	239.0	241.0	2.0	100	4A4	3.60	.07	3.46	8.20	80.0	.82	2.40	13.70	11.66	16.10	.70
FAGA111	14524	241.0	243.0	2.0	95	4A0	3.16	.05	1.61	2.57	30.0	.75	2.24	9.90	4.18	12.14	.61
FAGA111	14525	243.0	245.0	2.0	100	4A0	3.13	.04	1.31	1.57	23.0	.55	1.61	10.10	2.88	11.71	.55
FAGA111	14526	245.0	246.3	1.3	100	4A0	3.11	.06	1.08	1.74	18.0	.55	2.35	8.90	2.82	11.25	.62
FAGA111	14527	251.9	253.9	2.0	100	4D5	2.99	.02	1.91	3.66	30.0	.48	2.28	2.98	5.57	5.26	.66
FAGA111	14528	253.9	255.9	2.0	90	4D5	2.98	.02	2.27	3.74	35.0	.48	1.41	2.69	6.01	4.10	.62
FAGA111	14529	255.9	258.5	2.6	77	4D5	2.96	.02	2.15	4.57	35.0	.41	1.49	2.11	6.72	3.60	.68
FAGA111	14530	285.3	287.3	2.0	100	4A43	3.39	.13	4.14	8.44	66.0	.89	1.53	12.60	12.58	14.13	.67
FAGA111	14531	287.3	289.3	2.0	100	4A43	3.73	.19	4.54	4.93	63.0	1.17	1.18	19.90	9.47	21.08	.52
FAGA111	14532	289.3	290.9	1.6	81	4A43	3.39	.12	3.80	6.76	58.0	1.17	1.21	12.70	10.56	13.91	.64
FAGA111	14533	290.9	291.9	1.0	90	4A43	3.61	.21	4.06	5.53	64.0	1.65	1.22	19.20	9.59	20.42	.58
FAGA111	14534	291.9	293.2	1.3	100	4E46	4.68	.13	6.14	8.38	113.0	1.92	1.26	28.40	14.52	29.66	.58
FAGA111	14535	303.2	305.0	1.8	100	4E46	4.71	.14	6.39	11.00	142.0	1.71	1.20	28.80	17.39	30.00	.63

DDH	SAMPLE	---DEPTHS---		INT M	REC %	ROCK UNIT	S.G.	CU %	PB %	ZN %	AG G/MT	AU G/MT	PG %	PY %	BAO %	PB+ZN %	PO+PY %	ZN RATIO
		FROM	TO															
FAGA111	14536	305.0	307.5	2.5	96	4E46	4.76	.13	7.18	14.10	122.0	1.23	.95	18.60		21.28	19.55	.66
FAGA111	14537	307.5	308.3	.8	100	4G4	4.74	.12	6.54	13.80	115.0	1.23	.41	12.10		20.34	12.51	.68
FAGA111	14538	308.3	310.3	2.0	100	4E46	4.95	.09	9.37	13.60	158.0	1.09	.69	20.90		22.97	21.59	.59
FAGA111	14539	310.3	312.3	2.0	100	4E46	4.94	.19	5.58	9.10	105.0	1.92	.59	22.60		14.68	23.19	.62
FAGA111	14540	312.3	313.8	1.5	100	4E46	4.90	.21	6.86	10.10	112.0	2.19	.65	23.60		16.96	24.25	.60
FAGA111	14541	313.8	315.2	1.4	93	4E46	4.82	.12	12.90	20.00	199.0	2.13	1.84	17.70		32.90	19.54	.61
FAGA111	14542	369.3	371.6	2.3	87	4E4	5.08	.11	5.97	8.40	94.0	1.44	17.25	3.15		14.37	20.40	.58
FAGA111	14543	371.6	373.7	2.1	100	4A0	3.60	.03	1.40	2.46	26.0	.41	8.46	2.94		3.86	11.40	.64
FAGA140	14544	85.3	87.3	2.0	75	4A4	3.60	.01	6.49	18.60	113.0	.89	2.20	7.50		25.09	9.70	.74
FAGA140	14545	87.3	89.3	2.0	75	4A43	3.54	.01	3.08	8.70	52.0	.41	2.22	14.10		11.78	16.32	.74
FAGA118	14546	203.3	204.8	1.5	100	4A4	3.17	.03	2.68	4.74	40.0	.62	2.49	6.80		7.42	9.29	.64
FAGA118	14547	204.8	206.2	1.4	100	4A4	3.16	.05	3.23	5.60	43.0	.69	2.17	7.40		8.83	9.57	.63
FAGA118	14548	206.2	207.8	1.6	100	4A4	3.32	.01	1.45	3.76	19.0	.55	2.58	12.80		5.21	15.38	.72
FAGA118	14549	207.8	209.4	1.6	94	4A4	3.17	.03	2.54	3.45	30.0	.69	1.07	8.70		5.99	9.77	.58
FAGA118	14550	209.4	210.2	.8	87	3G96	2.95	.01	1.03	1.22	13.0	.34	.65	1.85		2.25	2.50	.54
FAGA118	14551	210.2	212.2	2.0	100	4A0	3.08	.05	1.25	1.23	16.0	.41	1.00	7.70		2.48	8.70	.50
FAGA118	14552	212.2	214.2	2.0	85	4A0		.05	.71	.62	12.0					1.33		.47
FAGA118	14553	214.2	215.1	.9	89	4A0		.06	3.02	1.07	41.0					4.09		.26
FAGA118	14554	215.1	217.0	1.9	74	4C0		.11	.54	.52	10.0					1.06		.49
FAGA118	14555	217.0	218.8	1.8	100	4A4	3.39	.04	3.45	5.90	52.0	.89	2.10	.96		9.35	3.06	.63
FAGA118	14556	218.8	220.0	1.2	100	4C5	2.96	.02	1.04	2.86	19.0	.21	2.51	1.29		3.90	3.80	.73
FAGA118	14557	226.0	228.0	2.0	100	4D5	3.19	.09	2.97	2.95	44.0	1.44	1.26	8.80		5.92	10.06	.50
FAGA118	14558	228.0	229.8	1.8	100	4D5	3.23	.06	4.14	3.93	57.0	1.03	2.80	7.60		8.07	10.40	.49
FAGA118	14559	229.8	231.0	1.2	100	4DH5	3.64	.11	4.10	6.45	72.0	.96	18.10	5.40		10.55	23.50	.61
FAGA118	14560	231.0	233.0	2.0	100	4A4	3.39	.09	6.06	10.10	107.0	1.23	1.51	8.00		16.16	9.51	.63
FAGA118	14561	233.0	234.7	1.7	88	4A4	3.13	.03	3.35	6.50	56.0	.75	1.32	5.00		9.85	6.32	.66
FAGA118	14562	240.4	242.2	1.8	100	4A4	3.26	.03	2.06	3.47	40.0	.75	1.60	11.40		5.53	13.00	.63
FAGA118	14563	242.2	243.2	1.0	100	3G96	3.07	.03	1.43	2.81	26.0	.14	4.13	3.97		4.24	8.10	.66
FAGA118	14564	243.2	245.2	2.0	95	4A0	3.24	.05	.91	1.41	25.0	.69	.93	13.20		2.32	14.13	.61
FAGA118	14565	245.2	247.2	2.0	100	4A0		.05	.48	.73	21.0					1.21		.60
FAGA118	14566	247.2	248.7	1.5	93	4A0		.03	.71	1.09	17.0					1.80		.61
FAGA118	14567	290.2	292.4	2.2	100	4D5	3.53	.07	4.46	4.41	70.0	1.10	1.18	14.90		8.87	16.08	.50
FAGA118	14568	298.6	300.6	2.0	100	4C5		.09	1.00	1.01	17.0					2.01		.50
FAGA118	14569	300.6	302.6	2.0	100	4C5		.03	.59	1.19	8.0					1.78		.67
FAGA118	14570	355.5	356.7	1.2	100	4A0	3.15	.08	1.19	1.44	22.0	.82	1.06	10.70		2.63	11.76	.55
FAGA118	14571	356.7	358.9	2.2	100	4E4	4.13	.17	3.03	3.44	57.0	.69	1.74	25.20		6.47	26.94	.53
FAGA118	14572	358.9	360.5	1.6	100	4A0	3.22	.13	1.60	3.11	27.0	.41	1.62	10.60		4.71	12.22	.66
FAGA118	14573	360.5	362.5	2.0	100	4A0	3.12	.05	1.31	2.57	24.0	.21	4.80	6.40		3.88	11.20	.66
FAGA118	14574	362.5	364.5	2.0	10	4A0		.01	.02	.05	1.0					.07		.71
FAGA118	14575	364.5	366.5	2.0	45	3G9		.01	.03	.07	1.0					.10		.71
FAGA118	14576	366.5	368.5	2.0	25	3G9		.01	.01	.04	1.0					.05		.80
FAGA118	14577	369.4	370.9	1.5	100	4E4	4.26	.10	4.04	6.71	77.0	.89	1.63	24.30		10.75	25.93	.62
FAGA118	14578	370.9	372.4	1.5	13	4E4	4.02	.06	3.34	3.92	63.0	.96	1.86	23.00		7.26	24.86	.54
FAGA118	14579	373.0	373.8	.8	75	4E4	4.51	.17	3.75	3.53	66.0	.34	2.80	30.50		7.28	33.30	.48
FAGA118	14580	373.8	375.3	1.5	100	4A3	3.53	.11	1.48	3.18	37.0	.41	1.51	16.60		4.66	18.11	.68
FAGA118	14581	375.3	377.0	1.7	94	4A3	3.37	.09	1.57	3.03	34.0	.55	1.24	15.80		4.60	17.04	.66
FAGA118	14582	377.0	379.6	2.6	100	4E4	4.52	.24	2.81	3.92	54.0	.62	1.49	34.20		6.73	35.69	.58
FAGA118	14583	379.6	382.2	2.6	100	4AE4	3.75	.25	3.29	5.96	62.0	1.92	2.26	19.30		9.25	21.56	.64
FAGA118	14589	417.6	419.0	1.4	93	4E4#		.19	3.60	4.38	56.0					7.98		.55
FAGA118	1459C	419.0	420.6	1.6	75	4L12		.06	.12	.13	5.0					.25		.52



DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAO	PB+ZN	PC+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGA104	14641	166.3	168.3	2.0	85	4A14	2.92	.02	2.08	4.85	35.0	.62	1.09	4.71		6.93	5.80	.70
FAGA104	14642	168.3	171.0	2.7	85	4A10	2.95	.02	1.72	2.18	23.0	.75	1.15	1.85		3.90	3.00	.56
FAGA104	14643	199.4	202.8	3.4	91	4A41	3.42	.05	5.10	8.80	85.0	1.30	1.86	11.00		13.90	12.86	.63
FAGA104	14644	202.8	204.8	2.0	100	4A14	3.13	.05	3.10	4.41	44.0	.75	1.80	7.20		7.51	9.00	.59
FAGA104	14645	204.8	206.7	1.9	100	4A14	3.03	.02	2.02	4.52	29.0	.82	2.05	2.85		6.54	4.90	.69
FAGA104	14646	362.2	364.2	2.0	75	4ACE		.09	.48	.67	11.0					1.15		.58
FAGA104	14647	364.2	366.2	2.0	90	4ACE		.10	.28	.42	7.0					.70		.60
FAGA104	14648	366.2	368.7	2.5	100	4ACE	3.63	.14	1.32	1.99	22.0	.96	2.01	19.60		3.31	21.61	.60
FAGA104	14649	391.6	393.1	1.5	93	4G4	4.62	.16	5.10	8.50	92.0	.75	.61	10.80		13.60	11.41	.63
FAGA104	14650	393.1	394.8	1.7	82	4AD	3.06	.07	1.46	2.82	26.0	.82	1.28	5.00		4.28	6.28	.66
FAGA104	14651	401.0	403.0	2.0	100	4ED	4.22	.17	2.00	2.18	28.0	1.10	3.72	24.80		4.18	28.52	.52
FAGA104	14652	403.0	404.5	1.5	73	4ED	4.55	.37	2.18	2.86	36.0	1.51	11.20	27.60		5.04	38.80	.57
FAGA104	14653	404.5	407.5	3.0	97	4GEL	3.71	.12	3.99	5.20	69.0	1.85	2.75	11.30		9.19	14.05	.57
FAGA156	14654	85.1	87.1	2.0	85	4A41	3.35	.04	2.98	5.00	46.0	1.03	2.76	12.10		7.98	14.86	.63
FAGA156	14655	87.1	88.7	1.6	100	4A41	3.20	.10	1.92	3.14	32.0	.89	5.40	8.40		5.06	13.80	.62
FAGA156	14656	88.7	89.7	1.0	90	4D0	3.21	.06	1.75	3.84	30.0	.75	5.47	10.10		5.59	15.57	.69
FAGA156	14657	91.3	92.4	1.1	91	4C0	2.98	.01	1.37	2.56	18.0	.48	2.92	4.08		3.93	7.00	.65
FAGA156	14658	95.9	97.4	1.5	100	4 ACD	3.10	.05	1.69	2.95	29.0	.41	2.36	2.94		4.64	5.30	.64
FAGA156	14659	97.4	98.9	1.5	100	4C0	2.91	.03	1.27	2.89	24.0	.62	1.89	1.21		4.16	3.10	.69
FAGA156	14660	98.9	100.9	2.0	70	4A1	3.01	.03	1.39	2.28	24.0	.55	2.67	2.23		3.67	4.90	.62
FAGA156	14661	100.9	103.4	2.5	76	4A14	3.16	.03	3.74	5.10	61.0	.41	1.14	4.76		8.84	5.90	.58
FAGA156	14662	103.4	104.2	.8	100	4D514	3.73	.04	3.45	7.20	67.0	.69	5.80	14.90		10.65	20.70	.68
FAGA156	14663	106.2	109.0	2.8	89	4A14	3.10	.04	1.88	4.30	31.0	.62	1.92	6.00		6.18	7.92	.70
FAGA156	14664	109.0	109.7	.7	100	4ACD	3.10	.03	1.41	2.91	29.0	.48	3.86	2.84		4.32	6.70	.67
FAGA156	14665	109.7	111.5	1.8	83	4A14	3.26	.10	4.16	5.90	61.0	.89	1.54	7.50		10.06	9.04	.59
FAGA156	14666	111.5	113.2	1.7	100	4A14	3.64	.09	3.65	4.32	55.0	.55	2.22	8.40		7.97	10.62	.54
FAGA156	14667	113.2	114.3	1.1	100	4A14	3.13	.05	2.97	4.34	51.0	.89	2.50	4.50		7.31	7.00	.59
FAGA156	14668	114.3	116.3	2.0	100	4D54	3.10	.06	4.02	6.40	65.0	1.30	1.49	2.31		10.42	3.80	.61
FAGA156	14669	116.3	118.3	2.0	100	4D5	3.03	.03	3.34	5.70	53.0	.55	1.42	1.88		9.04	3.30	.63
FAGA156	14670	118.3	119.5	1.2	100	4D5	3.03	.03	2.24	3.83	32.0	.48	1.98	2.22		6.07	4.20	.63
FAGA156	14671	122.3	124.0	1.7	76	4D5	2.95	.03	2.22	3.29	31.0	.34	1.39	1.71		5.51	3.10	.60
FAGA156	14672	124.0	126.3	2.3	96	4A14	3.25	.04	2.29	6.30	39.0	.41	1.88	5.50		8.59	7.38	.73
FAGA156	14673	126.3	128.3	2.0	55	4D0	3.06	.02	2.26	5.30	37.0	.27	2.80	2.40		7.56	5.20	.70
FAGA156	14674	128.3	130.6	2.3	57	4D0	3.08	.01	2.37	6.20	42.0	.01	2.81	2.70		8.57	5.51	.72
FAGA156	14675	132.7	134.2	1.5	93	4D5	3.11	.05	2.01	3.05	33.0	.41	4.46	5.00		5.06	9.46	.60
FAGA156	14676	134.2	135.3	1.1	91	5D*	3.05	.02	2.73	1.83	41.0	2.54	5.70	1.01		4.56	6.71	.40
FAGA156	14677	135.3	136.7	1.4	100	4D0	3.13	.03	3.31	5.20	51.0	.48	4.00	2.40		8.51	6.40	.61
FAGA156	14678	136.7	138.7	2.0	100	4A14	3.12	.04	2.70	3.92	39.0	.82	1.76	4.54		6.62	6.30	.59
FAGA156	14679	138.7	140.7	2.0	90	4A14	3.14	.04	2.68	4.60	50.0	.75	1.58	6.42		7.28	8.00	.63
FAGA156	14680	140.7	142.7	2.0	95	4A10	3.07	.03	1.57	3.39	31.0	.48	.97	5.03		4.96	6.00	.68
FAGA156	14681	142.7	144.7	2.0	100	4A10	3.06	.04	1.29	2.20	28.0	.48	.91	7.20		3.49	8.11	.63
FAGA156	14682	144.7	146.7	2.0	100	4A10	3.06	.03	1.38	3.01	27.0	.41	1.02	6.20		4.39	7.22	.69
FAGA156	14683	146.7	148.7	2.0	65	4A10	3.10	.03	1.47	1.43	27.0	.55	.93	8.60		2.90	9.53	.49
FAGA156	14684	148.7	150.7	2.0	90	4A10	3.23	.02	2.12	2.59	31.0	.69	1.53	7.40		4.71	8.93	.55
FAGA156	14685	150.7	154.7	4.0	80	4A10	3.20	.04	1.21	1.57	24.0	.48	1.53	7.40		2.78	8.93	.57
FAGA156	14687	154.7	156.7	2.0	95	4A14	3.30	.06	2.09	5.20	36.0	.48	1.49	10.50		7.29	11.99	.71
FAGA156	14688	156.7	157.9	1.2	100	4A10	3.01	.05	1.24	2.56	25.0	.34	1.40	10.50		3.80	11.90	.67
FAGA156	14689	169.8	170.7	.9	89	4D4	3.10	.02	3.33	11.20	77.0	.21	1.43	4.67		14.53	6.10	.77
FAGA156	14690	174.3	175.5	1.2	100	4A4	3.89	.04	3.44	8.90	72.0	1.10	2.25	1.25		12.34	3.50	.72
FAGA156	14691	175.5	177.0	1.5	100	4A10	3.06	.03	1.80	2.97	29.0	.48	2.90	19.70		4.77	22.60	.62

DDH	SAMPLE	---DEPTHS---	INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAO	PB+ZN	PG+PY	ZN
		FROM TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGA156	14692	194.3 196.3	2.0	90	4C5	3.25	.04	1.86	2.93	31.0	.75	3.28	4.52		4.79	7.80	.61
FAGA156	14693	196.3 198.3	2.0	90	4DA	3.24	.02	3.45	4.57	61.0	.96	1.70	10.60		8.02	12.30	.57
FAGA156	14694	198.3 200.3	2.0	95	4DA	3.24	.02	2.70	5.30	49.0	.75	1.50	9.90		8.00	11.40	.66
FAGA156	14695	200.3 201.5	1.2	100	4A14	3.16	.05	1.88	3.15	31.0	1.71	1.73	9.40		5.03	11.13	.63
FAGA156	14696	201.5 202.3	.8	88	4AG	3.03	.03	1.70	3.17	24.0	.48	2.78	7.40		4.87	10.18	.65
FAGA241	14697	150.6 151.8	1.2	100	3G91		.12	.09	.20	7.0					.29		.69
FAGA241	14698	151.8 152.9	1.1	100	3G91		.08	.06	.08	3.0					.14		.57
FAGA241	14699	152.9 153.9	1.0	100	4AE4	3.09	.02	2.16	4.01	34.0	.62	1.76	3.34		6.17	5.10	.65
FAGA241	14700	157.0 157.9	.9	100	4E46#	4.62	.16	3.09	3.64	44.0	.62	2.33	12.90		6.73	15.23	.54
FAGA241	14701	157.9 159.9	2.0	100	4G4#	4.68	.19	8.00	8.20	98.0	.62	4.01	32.30		16.20	36.31	.51
FAGA241	14702	159.9 161.8	1.9	100	4E4#	4.73	.16	7.20	8.10	100.0	.55	2.16	20.40		15.30	22.56	.53
FAGAG01	90000	262.5 263.3	.8		5B21		.25	1.45	1.28	20.2	.34				2.73		.47
FAGAG04	90001	199.9 201.5	1.6		4E4		.30	6.16	8.75	126.1	1.37				14.91		.59
FAGAG04	90002	201.5 203.0	1.5		4E4		.29	7.50	10.10	126.1	1.37				17.60		.57
FAGAG04	90003	203.0 204.5	1.5		4E4		.34	5.96	10.80	129.2	2.06				16.76		.64
FAGAG04	90004	204.5 205.9	1.4		4E4		.30	7.19	13.98	151.2	2.06				21.17		.66
FAGAG04	90005	205.9 208.0	2.1		4LD		.16	2.23	3.84	60.3	.34				6.07		.63
FAGAG05	90006	160.5 161.7	1.2		4E4		.25	6.50	21.50	113.8	.34				28.00		.77
FAGAG05	90007	161.7 163.7	2.0		4E4		.16	4.70	22.90	59.0	.34				27.60		.83
FAGAG05	90008	163.7 165.4	1.7		4E4		.32	9.20	15.50	176.2	.69				24.70		.63
FAGAG05	90009	165.4 166.0	.6		4E4		.06	.38	.38	9.6	.34				.76		.50
FAGAG05	90010	166.0 166.5	.5		4E4		.05	3.98	8.06	61.0	.69				12.04		.67
FAGAG05	90011	166.5 169.6	3.1		5B2		.06	.38	.62	2.7	.17				1.00		.62
FAGAG05	90012	169.6 170.5	.9		4E4		.19	4.05	6.85	77.5	.69				10.90		.63
FAGAG05	90013	170.5 171.8	1.3		4E4		.16	6.45	12.30	104.9	.69				18.75		.66
FAGAG05	90014	171.8 173.1	1.3		4E4		.28	6.60	13.10	152.2	.69				19.70		.66
FAGAG05	90015	173.1 174.3	1.2		4E4		.29	5.78	9.24	149.5	1.37				15.02		.62
FAGAG05	90016	174.3 175.9	1.6		4E4		.33	5.85	9.03	82.3	1.37				14.88		.61
FAGAG05	90017	175.9 177.1	1.2		4E4		.34	6.90	9.10	142.6	1.37				16.00		.57
FAGAG05	90018	177.1 178.8	1.7		4E4		.18	9.20	17.40	125.5	.69				26.60		.65
FAGAG05	90019	178.8 180.4	1.6		4A0		.05	1.13	2.28	16.5	.34				3.41		.67
FAGAG09	90020	113.9 115.5	1.6		4AL		.09	1.18	3.36	21.9	.34				4.54		.74
FAGAG09	90021	115.5 117.0	1.5		4L4		.03	.95	2.28	11.0	.17				3.23		.71
FAGAG09	90022	117.0 118.5	1.5		4A4		.03	2.23	5.28	62.4	.69				7.51		.70
FAGAG09	90023	118.5 120.0	1.5		4A4		.04	2.50	5.40	57.3	.34				7.90		.68
FAGAG09	90024	120.0 121.6	1.6		4LA		.05	2.03	4.20	38.4	.34				6.23		.67
FAGAG09	90025	121.6 123.1	1.5		4L1		.03	.98	1.40	19.2	.34				2.38		.59
FAGAG09	90026	123.1 124.6	1.5		4L1		.06	2.00	4.02	27.4	.34				6.02		.67
FAGAG09	90027	132.3 133.8	1.5		4A14		.08	2.85	6.12	57.6	.34				8.97		.68
FAGAG09	90028	133.8 135.3	1.5		4A14		.12	5.55	10.52	96.0	1.37				16.07		.65
FAGAG09	90029	135.3 136.9	1.6		4A14		.09	7.50	10.63	95.3	.69				18.13		.59
FAGAG09	90030	136.9 138.4	1.5		4A14		.10	7.35	11.88	103.2	1.03				19.23		.62
FAGAG09	90031	138.4 139.9	1.5		4A14		.05	2.45	5.16	74.7	.69				7.61		.68
FAGAG09	90032	139.9 141.5	1.6		4A14		.04	1.90	4.26	55.5	.69				6.16		.69
FAGAG14	90033	192.6 193.2	.6		4L24		.19	1.45	1.22	21.9	.34				2.67		.46
FAGAG14	90034	266.4 269.1	2.7		4A0		.16	.29	.42	31.5	.17				.71		.59
FAGAG14	90035	269.1 273.1	4.0		4A0		.16	.63	.69	37.0	.17				1.32		.52
FAGAG14	90036	273.1 275.8	2.7		4EG4		.30	6.53	6.96	91.5	.69				13.49		.52
FAGAG14	90037	275.8 278.9	3.1		4A0		.20	.55	.66	12.3	.17				1.21		.55

DDH	SAMPLE	----DEPTHS----		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAO	PB+ZN	PC+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGA014	90038	278.9	281.9	3.0		4A0		.17	2.00	2.76	53.5	.34				4.76		.58
FAGA014	90039	281.9	283.5	1.6		4A0		.15	.33	.46	21.9	.34				.79		.58
FAGA014	90040	283.5	287.1	3.6		4E0		.20	1.73	2.00	32.9	.17				3.73		.54
FAGA068	90041	128.5	129.8	1.3	100	4E4			7.71	12.62	105.9					20.33		.62
FAGA068	90042	188.7	190.2	1.5	100	4D0			3.30	4.80	40.4					8.10		.59
FAGA068	90043	203.5	205.2	1.7	94	4A4			8.00	7.80	110.0					15.80		.49
FAGA068	90044	205.2	206.8	1.6	100	4A4			8.15	15.38	121.0					23.53		.65
FAGA068	90045	206.8	208.0	1.2	100	4A4			3.30	5.22	64.5					8.52		.61
FAGA068	90046	215.3	217.4	2.1	100	4A4			7.63	9.81	102.8					17.44		.56
FAGA068	90047	217.4	219.3	1.9	100	4A4			10.23	19.00	141.2					29.23		.65
FAGA068	90048	219.3	219.9	.6	100	4A4			10.06	12.46	121.0					22.52		.55
FAGA068	90049	241.0	242.4	1.4	93	4EG4			4.73	6.00	75.8					10.73		.56
FAGA068	90050	242.4	244.0	1.6	100	4EG4			5.10	8.30	70.6					13.40		.62
FAGA068	90051	247.5	249.5	2.0	100	4E4			5.63	10.47	75.8					16.10		.65
FAGA073	90052	35.7	36.7	1.0	50	4A0			.54	1.04	8.9					1.58		.66
FAGA073	90053	36.7	38.4	1.7	59	4A0			1.43	2.73	24.3					4.16		.66
FAGA073	90054	38.4	39.3	.9	67	4A4			1.60	3.42	32.2					5.02		.68
FAGA073	90055	39.3	41.1	1.8	39	4A4			1.83	4.32	35.3					6.15		.70
FAGA073	90056	41.1	42.7	1.6	50	4A0			1.38	1.30	27.4					2.68		.49
FAGA073	90057	46.0	46.9	.9	89	4E4			3.60	9.54	66.5					13.14		.73
FAGA073	90058	75.3	77.1	1.8	94	5C3			.35	.42	3.1					.77		.55
FAGA073	90059	77.1	79.9	2.8	96	4E4			8.86	14.93	128.2					23.79		.63
FAGA073	90060	79.9	81.4	1.5	100	4D4			4.20	5.28	58.6					9.48		.56
FAGA073	90061	81.4	84.4	3.0	100	4D4			3.45	7.32	50.4					10.77		.68
FAGA073	90062	84.4	86.4	2.0	100	4D4			4.13	7.30	55.5					11.43		.64
FAGA073	90063	86.4	88.1	1.7	100	4D4			1.95	5.76	25.4					7.71		.75
FAGA073	90064	88.9	90.5	1.6	75	4A4			2.15	4.86	32.2					7.01		.69
FAGA073	90065	90.5	92.4	1.9	95	4A4			2.08	3.48	28.1					5.56		.63
FAGA073	90066	92.4	94.2	1.8	100	4A4			5.93	12.58	90.8					18.51		.68
FAGA073	90067	94.2	95.3	1.1	64	4A4			2.78	5.16	44.2					7.94		.65
FAGA073	90068	95.3	97.4	2.1	43	4A4			2.93	7.68	46.3					10.61		.72
FAGA073	90069	98.6	99.5	.9	44	5C24			1.00	4.26	18.2					5.26		.81
FAGA073	90070	100.1	100.6	.5	100	5C24			2.40	7.02	39.4					9.42		.75
FAGA073	90071	100.6	103.5	2.9	100	4D4			5.84	10.45	88.8					16.29		.64
FAGU114	90072	22.9	24.4	1.5	100	4A4			2.33	3.85	35.3					6.18		.62
FAGU005	90073	44.2	48.7	4.5		4A14			1.95	3.78	37.8					5.75		.60
FAGU006	90074	.0	2.4	2.4	17	4A14			2.85	3.65	40.5					6.50		.60
FAGU006	90075	6.0	9.1	3.1	94	4A14			2.28	4.58	34.3					6.86		.61
FAGU006	90076	14.4	15.2	.8	100	4A14			.95	2.70	15.4					3.65		.74
FAGU009	90077	31.0	32.0	1.0	50	3G46			2.10	2.00	35.3					4.10		.49
FAGU009	90078	32.0	33.0	1.0	100	4L4			2.20	2.98	34.3					5.18		.58
FAGU009	90079	38.1	39.5	1.4		3G4			.33	1.10	4.1					1.43		.77
FAGU016	90080	60.3	61.1	.8	100	10Q0			.75	1.05	17.1					1.80		.58
FAGUG25	90081	59.4	61.0	1.6	75	4D0			2.18	3.10	42.5					5.28		.59
FAGUG27	90082	94.7	96.0	1.3	62	4L4			2.23	3.60	33.3					5.83		.62
FAGU027	90083	99.1	100.6	1.5	73	4A1			1.20	2.35	18.2					3.55		.66
FAGU027	90084	100.6	102.1	1.5	73	4A14			2.80	3.30	34.3					6.10		.54
FAGU027	90085	102.1	103.5	1.4	71	4A1			.90	2.33	12.0					3.23		.72
FAGU004	90086	6.9	10.6	3.7		4A24			2.98	4.95	40.5					7.93		.62
FAGU004	90087	10.6	14.2	3.6		4A24			2.68	4.63	38.4					7.31		.63

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAO	PB+ZN	PC+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGU004	9C088	14.2	14.9	.7		4A2			1.13	2.10	19.2					3.23		.65
FAGU004	9C089	14.9	15.5	.6		4A24			2.40	3.80	39.4					6.20		.61
FAGA021	9C090	100.1	101.1	1.0	90	5B20		.02	.03	.10						.13		.77
FAGA021	9C091	101.1	103.5	2.4	83	4E4		.08	5.78	11.35	79.5	.69				17.13		.66
FAGA021	9C092	103.5	104.3	.8	87	5D4*		.02	.10	.30						.40		.75
FAGA021	9C093	104.3	107.1	2.8	75	4AE4		.15	8.25	14.83	149.5	.69				23.08		.64
FAGA021	9C094	107.1	109.4	2.3	78	4AL		.03	2.23	4.26	32.2	.17				6.49		.66
FAGA021	9C095	109.4	112.4	3.0	63	4A4		.06	4.43	8.76	56.2	.34				13.19		.66
FAGA021	9C096	112.4	113.7	1.3	100	4LA4		.06	3.75	1.44	39.8	.34				5.19		.28
FAGA021	9C097	113.7	115.2	1.5	93	4A4		.05	4.20	1.50	45.9	.34				5.70		.26
FAGA021	9C098	115.2	117.4	2.2	100	4A0		.08	.68	1.74	9.6	.17				2.42		.72
FAGA021	9C099	117.4	119.1	1.7	100	4A0		.08	.64	1.66	9.6	.17				2.30		.72
FAGA021	9C100	119.1	121.1	2.0	100	4L34		.10	.70	1.34	11.0	.17				2.04		.66
FAGA021	9C101	121.1	123.2	2.1	81	4L34		.08	.63	1.14	10.3	.17				1.77		.64
FAGA021	9C102	132.3	133.8	1.5	100	5B6		.02	.03	.05		.17				.08		.63
FAGA021	9C103	167.0	168.6	1.6	87	5B26		.02	.08	.33						.41		.80
FAGA021	9C104	179.8	181.2	1.4	100	4L0		.03	.08	.10	8.9					.18		.56
FAGA021	9C105	181.2	183.3	2.1	95	4EA4		.12	2.43	4.74	42.5	.34				7.17		.66
FAGA021	9C106	183.3	185.3	2.0	85	4E4		.09	3.08	5.04	48.0	.34				8.12		.62
FAGA021	9C107	185.3	186.8	1.5	100	4E4		.09	2.50	4.20	52.1	.34				6.70		.63
FAGA021	9C108	186.8	189.9	3.1	100	4E4		.12	4.43	8.76	71.3	.69				13.19		.66
FAGA021	9C109	189.9	192.9	3.0	100	4EG4		.04	4.28	9.12	76.8	.69				13.40		.68
FAGA021	9C110	192.9	194.5	1.6	100	4EG4		.17	5.03	9.36	83.6	.69				14.39		.65
FAGA021	9C111	194.5	196.0	1.5	100	4E4		.17	6.83	11.50	128.9	1.37				18.33		.63
FAGA021	9C112	196.0	197.5	1.5	100	4E4		.15	2.25	4.26	51.4	.69				6.51		.65
FAGA060	9C113	116.3	116.6	.3	100	4L0			.68	.51	19.2					1.19		.43
FAGA060	9C114	259.7	262.1	2.4	88	5B6			.07	.04						.11		.36
FAGA060	9C115	339.7	340.2	.5	100	5B26			1.63	.66	27.4					2.29		.29
FAGA013	9C117	44.0	48.3	4.3	100	4G4		.16	8.10	8.40	107.0	1.27				16.50		.51
FAGA013	9C118	48.3	52.3	4.0	100	4G4		.19	7.65	5.52	92.6	1.71				13.17		.42
FAGA013	9C119	54.9	59.0	4.1	100	4E0		.21	5.03	4.20	91.9	.69				9.23		.46
FAGA013	9C120	59.0	60.1	1.1	100	4E0		.15	1.50	1.90	29.5	.17				3.40		.56
FAGA013	9C121	60.1	61.6	1.5	100	4E4		.20	5.25	5.40	71.3	1.37				10.65		.51
FAGA013	9C122	61.6	64.2	2.6	100	4K0		.08	1.25	.16	33.9	1.02				1.41		.11
FAGA013	9C123	64.2	66.8	2.6	100	4K0		.20	1.63	.90	53.5	.69				2.53		.36
FAGA013	9C124	121.3	123.1	1.8	100	5A0		.03	.90	2.00	24.7	.34				2.90		.69
FAGA017	9C125	232.0	235.0	3.0	100	4E71		.30	2.00	1.58	34.3	.17				3.58		.44
FAGA017	9C126	235.0	237.1	2.1	100	4E71		.22	.30	.30	11.0	.34				.60		.50
FAGA017	9C127	237.1	239.0	1.9	100	4G4		.23	6.38	7.92	87.8	1.02				14.30		.55
FAGA023	9C134	221.9	224.3	2.4		4L0			.03	.03	2.1					.06		.50
FAGA023	9C135	245.2	246.9	1.7		4L0			.32	.76	5.1					1.08		.70
FAGA055	9C136	174.7	175.2	.5		5B6			1.08	2.76	17.1					3.84		.72
FAGA096	9C138	148.4	149.1	.7		4D4			9.63	22.37	177.6					32.00		.70
FAGA096	9C139	149.1	150.3	1.2		4D4			7.53	17.61	125.1					25.14		.70
FAGA096	9C140	150.3	151.5	1.2		4D4			7.20	17.92	142.3					25.12		.71
FAGA070	9C141	61.4	62.0	.6		4A4			4.58	8.00	60.3					12.58		.64
FAGA070	9C142	79.2	81.7	2.5		4LA			1.88	4.38	30.2					6.26		.70
FAGA070	9C143	64.8	66.6	1.8		4AE4			6.59	14.70	112.8					21.29		.69
FAGU003	9C144	64.0	65.4	1.4	86	4L0			1.00	1.30	15.1					2.30		.57

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAO	PB+ZN	PC+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGU003	90145	65.4	66.7	1.3	100	4LD			7.04	5.65	88.8					12.69		.45
FAGAG88	90146	116.4	118.1	1.7	88	4EA4			5.70	9.55	79.5					15.25		.63
FAGA088	90147	118.1	120.1	2.0	75	4EA4			2.00	3.90	22.3					5.90		.66
FAGA088	90148	204.1	204.8	.7	43	4A4			4.28	6.55	57.6					10.83		.60
FAGA088	90149	204.8	205.7	.9	89	4DE4			5.68	8.77	80.6					14.45		.61
FAGA088	90150	205.7	208.0	2.3	100	4DE4			7.87	10.83	103.9					18.70		.58
FAGA088	90151	208.0	208.8	.8	75	4DE4			5.03	5.40	57.6					10.43		.52
FAGA088	90152	209.4	210.0	.6	83	4DE4			5.64	6.24	67.5					11.88		.53
FAGA088	90153	327.4	329.2	1.8	100	4L2			.13	.37	4.1					.50		.74
FAGA157	90154	67.6	70.7	3.1	19	4LEA			1.00	.60	13.0					1.60		.38
FAGA066	90155	68.3	70.0	1.7		4A4			2.10	4.44	23.3					6.54		.68
FAGA066	90156	88.6	89.5	.9		4A34			5.63	5.52	61.4					11.15		.50
FAGA066	90157	106.2	107.2	1.0		4DEA4			4.65	5.82	54.4					10.47		.56
FAGA066	90158	156.4	158.2	1.8		4E#4			1.75	3.00	25.4					4.75		.63
FAGA066	90159	158.2	159.6	1.4		4E#4			5.70	7.20	72.7					12.90		.56
FAGA045	90160	50.9	51.8	.9	100	4B0			.73	3.18	9.9					3.91		.81
FAGA153	90161	58.3	60.0	1.7	100	4A0			1.18	1.40	15.1					2.58		.54
FAGA045	90162	66.4	67.2	.8	75	10G0			2.30	4.42	19.2					6.72		.66
FAGA045	90163	177.7	178.8	1.1	82	5D4*			1.48	.86	19.2					2.34		.37
FAGAC52	90164	78.0	78.3	.3	67	5B69			11.00	20.45	171.4					31.45		.65
FAGA052	90165	85.0	85.9	.9	67	5B69			1.75	2.22	27.4					3.97		.56
FAGA052	90166	86.1	87.6	1.5		4DGL			8.18	10.72	110.0					18.90		.57
FAGU100	90170	80.2	82.0	1.8	89	4A4			2.20	5.20	31.2					7.40		.70
FAGA134	90171	65.7	66.4	.7	100	5B9			1.20	1.40	17.1					2.60		.54
FAGA134	90172	66.4	67.9	1.5	100	4G41			7.56	9.70	99.8					17.26		.56
FAGA147	90173	136.2	137.8	1.6	100	4L0			.22	.53	3.1					.75		.71
FAGA147	90174	159.0	160.7	1.7	88	5A1			.07	.20	3.1					.27		.74
FAGA021	90175	197.5	198.7	1.2	100	4A4		.12	5.18	9.00	45.3	.34				14.18		.63
FAGA083	90176	240.4	241.1	.7	100	4A1			.10	.46	5.1					.56		.82
FAGA132	90177	93.2	94.5	1.3	100	4L0			.70	1.65	7.2					2.35		.70
FAGA132	90178	133.4	134.9	1.5	100	4A4			4.48	10.56	74.7					15.04		.70
FAGAG19	90179	102.4	103.8	1.4	100	4C0		.22	1.85	1.92	47.3	.69				3.77		.51
FAGAG19	90180	103.8	105.3	1.5	100	4C0		.13	1.18	1.02	11.0	.17				2.20		.46
FAGA019	90181	105.3	108.2	2.9	100	4CG4		.11	6.68	5.64	109.0	.69				12.32		.46
FAGA019	90182	134.7	135.9	1.2	100	5AD		.02	.05	.17	1.4	.17				.22		.77
FAGA019	90183	137.8	139.6	1.8	100	4A13		.17	1.15	2.00	31.5	.69				3.15		.63
FAGA019	90184	139.6	142.4	2.8	100	4E0		.34	.38	.60	21.9	.34				.98		.61
FAGA019	90185	142.4	145.5	3.1	97	4ED4		.07	7.35	9.36	139.9	1.37				16.71		.56
FAGA019	90186	145.5	147.8	2.3	100	4C0		.18	.25	.82	14.4	.69				1.07		.77
FAGA019	90187	147.8	150.3	2.5	100	4C0		.14	2.28	1.60	34.3	.34				3.88		.41
FAGAG19	90188	150.3	152.4	2.1	100	4A13		.06	4.95	6.96	60.3	.34				11.91		.58
FAGA019	90189	161.9	163.7	1.8	17	4L14		.11	2.25	4.68	58.3	.69				6.93		.68
FAGA019	90190	163.7	164.6	.9	56	4E4		.23	4.35	6.84	56.2	.69				11.19		.61
FAGA019	90191	164.6	165.5	.9	89	4E4		.21	7.55	12.72	111.8	.69				20.27		.63
FAGA019	90192	165.5	166.7	1.2	100	4E4		.11	3.15	4.74	50.1	.69				7.89		.60
FAGA019	90193	166.7	168.2	1.5	80	4E4		.11	2.05	3.72	38.4	.69				5.77		.64
FAGA019	90194	168.2	169.8	1.6	100	4E4		.10	2.28	3.90	53.5	.69				6.18		.63
FAGAG19	90195	169.8	171.3	1.5	100	4E4		.10	2.50	6.24	52.1	.69				8.74		.71
FAGA019	90196	171.3	172.8	1.5	100	4E4		.18	4.50	9.48	76.8	.69				13.98		.68
FAGA019	90197	172.8	174.4	1.6	100	4E4		.25	4.74	8.64	76.8	.69				13.38		.65

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAO	PB+ZN	PO+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGA019	90198	174.4	175.9	1.5	100	4E4		.17	5.78	10.20	109.7	1.37				15.98		.64
FAGA019	90199	175.9	176.7	.8	100	4E4		.05	3.08	5.76	67.9	.69				8.84		.65
FAGA019	90200	176.7	177.8	1.1	100	4L14		.03	1.85	3.33	46.6	.34				5.18		.64
FAGA019	90201	194.2	197.2	3.0	97	4D45		.20	9.15	15.36	137.8	2.06				24.51		.63
FAGA019	90202	197.2	198.4	1.2	100	4E1		.29	1.90	2.88	27.4	.34				4.78		.60
FAGA019	90203	198.4	200.9	2.5	100	4E14		.26	5.70	9.49	90.5	1.37				15.19		.62
FAGA019	90204	200.9	202.5	1.6	100	4E14		.33	2.70	3.30	50.7	1.37				6.00		.55
FAGA019	90205	202.5	205.3	2.8	100	4E14		.29	2.93	4.14	55.9	.69				7.07		.59
FAGA019	90206	207.6	208.4	.8	100	4A13		.42	.08	.37	16.5	.34				.45		.82
FAGU007	90207	10.7	11.2	.5		4A14			3.40	1.53	46.3					4.93		.31
FAGU007	90208	15.2	19.8	4.6	9	4A14			2.93	2.43	45.3					5.36		.45
FAGU007	90209	19.8	21.4	1.6	100	4A1			.39	.90	8.9					1.29		.70
FAGU007	90210	21.4	23.0	1.6	94	4A1			.68	1.00	11.0					1.68		.60
FAGU007	90211	32.0	35.0	3.0		4L24			1.65	2.45	28.5					4.10		.60
FAGU007	90212	35.0	35.7	.7		4L12			3.38	5.09	56.6					8.47		.60
FAGU007	90213	53.8	54.7	.9	89	4E4			7.39	12.72	128.2					20.11		.63
FAGU007	90214	54.7	56.1	1.4	100	4A13			3.00	4.00	44.2					7.00		.57
FAGA056	90215	104.0	106.1	2.1	10	F			1.98	3.54	30.2					5.52		.64
FAGA056	90216	185.5	186.0	.5	100	4L04			1.08	1.80	15.1					2.88		.63
FAGU018	90217	57.6	58.1	.5		4L0			.75	1.05	17.1					1.80		.58
FAGU018	90218	79.9	80.4	.5		4A14			3.30	4.00	45.3					7.30		.55
FAGU022	90219	3.0	4.6	1.6	100	4A1			1.63	2.03	24.3					3.66		.55
FAGU022	90220	10.7	12.2	1.5	100	4A1			3.40	1.25	37.4					4.65		.27
FAGU022	90221	21.3	22.2	.9	100	4A1			2.20	.93	24.3					3.13		.30
FAGU022	90222	22.2	22.9	.7	100	4A14			4.00	2.20	50.4					6.20		.35
FAGU023	90223	.0	1.9	1.9	32	4A1			2.03	2.55	24.3					4.58		.56
FAGU023	90224	22.3	23.9	1.6	94	4A1			1.94	2.50	15.1					4.44		.56
FAGU023	90225	67.1	67.8	.7	100	4A1			.48	.93	16.1					1.41		.66
FAGU086	90226	84.0	85.3	1.3	100	4L3			.78	.52	9.9					1.30		.40
FAGA062	90227	166.0	167.0	1.0		4L4			1.12	1.14	12.0					2.26		.50
FAGU088	90228	44.2	45.7	1.5		4E4			5.65	7.90	79.5					13.55		.58
FAGU088	90229	54.6	56.2	1.6		4L34			2.83	4.15	41.5					6.98		.59
FAGU098	90232	.0	2.0	2.0		4E0			4.75	8.61	70.6					13.36		.64
FAGU098	90233	2.0	3.8	1.8		4D4			8.37	19.67	145.0					28.04		.70
FAGU098	90234	3.8	5.8	2.0		4D4			9.17	23.91	152.2					33.08		.72
FAGU098	90235	5.8	8.1	2.3		4LE			2.10	4.65	43.5					6.75		.69
FAGU098	90236	8.1	10.2	2.1		4E4			7.02	9.74	121.0					16.76		.58
FAGU098	90237	10.2	12.6	2.4		4DL			5.46	11.55	76.8					17.01		.68
FAGU098	90238	12.6	14.2	1.6		4EK			3.10	4.05	46.3					7.15		.57
FAGU098	90239	14.2	15.6	1.4		4E4			5.26	7.44	94.6					12.70		.59
FAGU098	90240	15.6	17.1	1.5		4A4			2.68	4.70	45.3					7.38		.64
FAGU098	90241	17.1	18.3	1.2		4A0			1.13	1.78	14.1					2.91		.61
FAGU098	90242	21.5	22.9	1.4		4AC			.68	1.30	9.9					1.98		.66
FAGU098	90243	22.9	23.4	.5		4A0			.73	.75	18.2					1.48		.51
FAGU098	90244	23.4	25.9	2.5		4A0			1.80	2.80	29.1					4.60		.61
FAGU098	90245	25.9	27.4	1.5		4A4			3.78	7.05	46.3					10.83		.65
FAGU102	90246	27.4	29.0	1.6		4L4			2.58	4.00	44.2					6.58		.61
FAGU102	90247	29.0	33.5	4.5		4L4			2.58	4.40	35.3					6.98		.63
FAGU102	90248	37.9	39.2	1.3		4DL			2.48	6.25	27.4					8.73		.72
FAGU106	90249	15.2	16.8	1.6		4A0			.30	.45	6.2					.75		.60



DDH	SAMPLE	----DEPTHS----		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAO	PB+ZN	PC+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGA024	90300	228.9	229.5	.6		4L0		.50	2.50	4.92	70.6					7.42		.66
FAGA024	90301	229.5	229.8	.3		4L0		.50	.08	.34	3.1					.42		.81
FAGA024	90302	229.8	231.0	1.2		4C0		.50	4.65	8.52	96.7					13.17		.65
FAGA024	90303	231.0	233.8	2.8		5A3		.50	.13	.19	4.1					.32		.59
FAGA024	90304	249.6	251.8	2.2		5A3		.50	.05	.11	2.1					.16		.69
FAGA024	90305	253.5	254.9	1.4		5A1		.50	.05	.10	1.0					.15		.67
FAGA024	90306	254.9	257.3	2.4		0Q0		.50	1.28	2.28	35.3					3.56		.64
FAGA024	90307	343.6	345.2	1.6		5B6		.50	.08	.13	2.1					.21		.62
FAGA004	90308	146.8	149.8	3.0		5B46		.04	.10	.16	2.1	.17				.26		.62
FAGA004	90309	157.0	160.6	3.6		5B2		.08	.30	.25	4.1	.17				.55		.45
FAGAC05	90310	155.9	159.0	3.1		5B26		.04	.20	.31	.2					.51		.61
FAGU116	90311	5.4	7.1	1.7	47	5A69			.02	.05	1.0					.07		.71
FAGA011	90342	123.9	127.7	3.8		4L0		.21	1.95	1.26	38.4	.34				3.21		.39
FAGA011	90343	135.9	138.2	2.3		4LH		.03	.28	.27	7.5					.55		.49
FAGA011	90344	150.4	152.4	2.0		4EL4		.15	4.88	3.84	32.9	.34				8.72		.44
FAGA011	90345	152.4	154.2	1.8		4EL4		.20	4.20	3.90	26.7	.17				8.10		.48
FAGA011	90346	178.0	180.3	2.3		4GE4		.15	6.00	9.40	112.4	1.37				15.40		.61
FAGA011	90347	180.2	182.6	2.4		4G4		.20	8.74	13.50	156.3	1.37				22.24		.61
FAGUG35	90348	51.0	52.1	1.1	100	4A96			2.58	5.87	41.5					8.45		.69
FAGUC39	90349	4.1	6.2	2.1	100	5C4*			.14	.08	3.1					.22		.36
FAGU045	90350	61.5	62.5	1.0		4L2												
FAGU084	90351	6.3	10.2	3.9	90	4L0			.05	.14	.3					.19		.74
FAGU084	90352	12.4	13.1	.7	86	4L3			.10	2.10	2.1					2.20		.95
FAGUC84	90353	16.7	17.1	.4	100	4L0			.05	.22	2.1					.27		.81
FAGA099	90357	62.4	64.0	1.6	100	4A4			1.33	4.38	21.3					5.71		.77
FAGA139	90358	121.1	122.5	1.4	79	4L0			.03	.08	1.0					.11		.73
FAGA084	90367	215.6	216.7	1.1		4L14			3.08	4.86	45.3					7.94		.61
FAGAC84	90368	216.7	219.2	2.5		4G4			5.63	8.88	91.9					14.51		.61
FAGA084	90369	253.4	254.6	1.2		5B49			1.30	1.84	20.2					3.14		.59
FAGA084	90370	254.6	255.8	1.2		4E47			4.93	5.10	54.5					10.03		.51
FAGA072	90371	154.3	156.4	2.1		4AE			9.53	18.11	126.1					27.64		.66
FAGA072	90372	156.4	156.7	.3		4AE			5.64	12.45	79.5					18.09		.69
FAGA072	90373	160.9	162.0	1.1		4A34			2.15	4.20	30.2					6.35		.66
FAGA072	90374	185.5	186.2	.7		4A4			4.73	4.98	82.6					9.71		.51
FAGAC82	90375	333.3	334.8	1.5		4E81			2.20	3.78	23.3					5.98		.63
FAGA082	90376	334.8	336.3	1.5		4C78			1.45	2.73	18.2					4.18		.65
FAGA082	90377	114.3	115.8	1.5		4A4			1.63	3.60	33.3					5.23		.69
FAGA087	90390	163.6	165.0	1.4	100	4D4			5.37	9.26	81.6					14.63		.63
FAGA087	90391	165.0	165.7	.7	86	4D4			4.35	5.60	70.6					9.95		.56
FAGA087	90392	165.7	166.4	.7	100	4A4			2.93	3.12	45.3					6.05		.52
FAGA087	90393	178.7	179.6	.9	100	4A4			3.45	5.64	55.5					9.09		.62
FAGA087	90394	199.2	202.2	3.0	97	4D5			3.00	4.26	41.5					7.26		.59
FAGA087	90395	202.2	203.0	.8	100	4D5			2.00	2.22	26.4					4.22		.53
FAGA087	90396	203.0	206.0	3.0	100	4D5			3.08	3.90	43.5					6.98		.56
FAGA087	90397	219.9	222.8	2.9	100	4D0			3.90	3.48	75.8					7.38		.47
FAGA087	90398	222.8	225.7	2.9	100	4D0			2.38	6.66	42.5					9.04		.74
FAGA087	90399	229.8	232.0	2.2	95	4D4			4.20	8.36	75.8					12.56		.67

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAO	PB+ZN	PC+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGA087	90400	232.0	233.5	1.5	100	400			2.08	7.26	45.3					9.34		.78
FAGA087	90401	237.3	239.3	2.0	95	4E4			7.33	14.54	112.4					21.87		.66
FAGA087	90402	317.6	319.4	1.8	100	4GE4			4.13	6.15	82.6					10.28		.60
FAGA087	90403	319.4	320.9	1.5	93	4GE4			4.80	7.70	111.1					12.50		.62
FAGAG87	90404	320.9	322.6	1.7	100	4GE			3.15	5.16	52.4					8.31		.62
FAGA087	90405	322.6	323.0	.4	75	4E0			2.78	.50	50.4					3.28		.15
FAGA087	90406	323.7	324.1	.4	100	4E0			.11	.04	4.2					.15		.27
FAGA087	90407	324.1	326.9	2.8	100	4G4			4.28	5.28	71.7					9.56		.55
FAGA087	90408	326.9	327.5	.6	100	4E0			.73	.28	21.3					1.01		.28
FAGA087	90409	328.8	330.6	1.8	94	4A4			5.71	6.48	85.7					12.19		.53
FAGA087	90410	330.6	331.9	1.3	100	4GE4			4.58	7.68	72.7					12.26		.63
FAGA087	90411	331.9	335.0	3.1	97	4GE4			4.73	8.48	85.7					13.21		.64
FAGA087	90412	335.0	337.0	2.0	95	4A34			4.65	10.07	95.6					14.72		.68
FAGA087	90413	337.0	337.6	.6	100	4AL			.75	1.42	14.1					2.17		.65
FAGA085	90414	196.9	198.9	2.0		400			.25	.62	6.2					.87		.71
FAGA085	90415	198.9	201.9	3.0		400			.40	1.08	8.9					1.48		.73
FAGAG85	90416	201.9	205.0	3.1		4C5			.83	.94	13.0					1.77		.53
FAGA085	90417	205.0	208.0	3.0		4C5			.43	.68	5.1					1.11		.61
FAGAG85	90418	208.0	211.1	3.1		4C5			.44	1.14	6.2					1.58		.72
FAGA085	90419	211.1	214.1	3.0		400			.44	1.10	5.1					1.54		.71
FAGAG85	90420	214.1	217.2	3.1		400			.80	1.16	12.0					1.96		.59
FAGA085	90421	217.2	218.8	1.6		400			2.48	5.82	34.3					8.30		.70
FAGA085	90422	219.9	221.9	2.0		3G0			.19	.33	1.0					.52		.63
FAGA085	90423	221.9	224.5	2.6		3G0			.22	.48	2.1					.70		.69
FAGA085	90424	258.0	261.1	3.1		400			.60	1.10	9.9					1.70		.65
FAGA085	90425	261.1	262.7	1.6		400			.38	.61	7.2					.99		.62
FAGA085	90426	262.7	264.6	1.9		4A4			3.83	3.96	47.3					7.79		.51
FAGA085	90427	264.6	266.2	1.6		4A4			2.38	3.72	30.2					6.10		.61
FAGAG85	90428	266.2	268.6	2.4		4A4			4.73	5.40	65.5					10.13		.53
FAGAG85	90429	268.6	270.6	2.0		4A0			.98	1.68	17.1					2.66		.63
FAGA085	90430	270.6	273.6	3.0		400			.34	.28	6.2					.62		.45
FAGA085	90431	273.6	277.7	4.1		4A0			1.20	1.42	23.3					2.62		.54
FAGA085	90432	281.6	284.7	3.1		4A30			1.38	1.40	21.3					2.78		.50
FAGAG85	90433	292.9	296.0	3.1		4A4			4.13	3.96	45.3					8.09		.49
FAGA085	90434	299.3	302.8	3.5		4A4			2.78	2.82	36.3					5.60		.50
FAGA085	90435	338.1	340.9	2.8		4D4			4.43	6.75	65.5					11.18		.60
FAGAG85	90436	340.9	343.8	2.9		4D43			5.25	6.96	65.5					12.21		.57
FAGA085	90437	343.8	346.3	2.5		4D43			5.23	11.53	80.6					16.76		.69
FAGA085	90438	346.3	347.5	1.2		4D43			4.85	7.48	64.5					12.33		.61
FAGA085	90439	348.1	351.1	3.0		4D43			5.98	9.03	80.6					15.01		.60
FAGA085	90440	351.1	352.3	1.2		4E4			4.54	7.68	55.5					12.22		.63
FAGAG85	90441	357.0	357.8	.8		4D45			6.35	9.97	90.8					16.32		.61
FAGAG85	90442	360.6	361.6	1.0		400			3.87	4.62	61.4					8.49		.54
FAGA085	90443	366.5	368.5	2.0		4L57			.43	.26	7.2					.69		.38
FAGA085	90444	368.5	369.1	.6		4L57			.65	1.13	14.1					1.78		.63
FAGA085	90445	390.8	391.5	.7		4A0			.63	1.06	8.9					1.69		.63
FAGA085	90446	391.5	392.4	.9		4E47			5.12	3.96	50.7					9.08		.44
FAGAG85	90447	393.5	395.2	1.7		4E4			4.65	3.66	51.4					8.31		.44
FAGA085	90448	400.2	400.7	.5		4E80			2.78	2.76	35.3					5.54		.50
FAGA085	90449	239.6	242.8	3.2		4D5			3.00	3.96	36.3					6.96		.57

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAO	PB+ZN	PC+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGA089	90450	343.0	344.4	1.4		4A0			.05	.36	1.0					.41		.88
FAGA089	90451	344.4	347.7	3.3		4A0			.21	.38	8.2					.59		.65
FAGA089	90452	347.7	349.8	2.1		4C0			.03	.03	1.0					.06		.50
FAGA089	90453	352.7	356.7	4.0		4A0			.08	.14	3.1					.22		.64
FAGA089	90455	356.7	357.6	.9		4C0			.09	.16	1.0					.25		.65
FAGA089	90456	377.2	378.0	.8	100	4E0			.70	.52	19.2					1.22		.43
FAGA093	90457	289.3	289.7	.4		4E4			4.88	4.56	75.8					9.44		.48
FAGA093	90458	289.7	290.8	1.1		4L12			4.88	4.56	75.8					9.44		.48
FAGA089	90459	163.7	165.5	1.8		4CE			.93	1.74	15.1					2.67		.65
FAGA089	90460	165.5	168.0	2.5		4EC			1.13	1.14	22.3					2.27		.50
FAGA089	90461	259.0	260.7	1.7		4D4#\$			5.03	9.50	72.7					14.53		.65
FAGA075	90462	26.2	27.7	1.5	100	4A4			2.28	5.58	40.4					7.86		.71
FAGA075	90463	27.7	29.0	1.3	100	4A4			1.60	3.84	26.1					5.44		.71
FAGA075	90464	29.0	30.5	1.5	100	4A4			2.00	4.02	31.2					6.02		.67
FAGA075	90465	30.5	32.6	2.1	100	4A4			1.85	3.90	30.2					5.75		.68
FAGA075	90466	32.6	35.1	2.5	100	4AL			1.23	3.30	15.1					4.53		.73
FAGA075	90467	35.1	36.0	.9	100	4L14			2.20	3.48	34.3					5.68		.61
FAGA075	90468	36.0	37.5	1.5	100	4L14			2.35	4.32	31.2					6.67		.65
FAGA075	90469	37.5	39.0	1.5	100	4L14			1.65	3.06	24.3					4.71		.65
FAGA075	90470	39.0	40.8	1.8	100	4A4			1.23	4.59	18.2					5.82		.79
FAGA075	90471	40.8	42.1	1.3	100	4A4			2.18	5.88	31.2					8.06		.73
FAGA075	90472	42.1	43.6	1.5	100	4A0			1.48	3.48	24.3					4.96		.70
FAGA075	90473	43.6	44.8	1.2	100	4A4			1.63	3.78	24.3					5.41		.70
FAGA075	90474	44.8	45.9	1.1	100	4A4			2.20	5.76	39.4					7.96		.72
FAGA075	90475	45.9	47.2	1.3	100	5D4a			.34	1.90	6.2					2.24		.85
FAGA075	90476	47.2	48.8	1.6	100	4AD			3.30	5.22	50.4					8.52		.61
FAGA075	90477	48.8	50.4	1.6	100	4C0			.28	.96	5.1					1.24		.77
FAGA075	90478	50.4	51.5	1.1	100	4D0			2.93	5.88	45.3					8.81		.67
FAGA075	90479	53.6	56.7	3.1	100	4A0			1.60	1.96	21.3					3.56		.55
FAGA075	90480	56.7	58.8	2.1	100	4A0			1.48	3.36	22.3					4.84		.69
FAGA075	90481	58.8	59.6	.8	100	4A4			1.93	4.50	34.3					6.43		.70
FAGA075	90482	59.6	61.3	1.7	100	4A4			3.90	9.08	64.5					12.98		.70
FAGA075	90483	61.3	62.8	1.5	100	4A4			3.15	5.16	43.2					8.31		.62
FAGA075	90484	62.8	64.9	2.1	100	4A4			4.35	6.36	57.6					10.71		.59
FAGA075	90485	64.9	67.7	2.8	100	4A4			1.95	3.30	30.2					5.25		.63
FAGA075	90486	68.4	69.8	1.4	100	4L41			2.85	4.50	37.4					7.35		.61
FAGA075	90487	69.8	71.6	1.8	100	4AL			2.13	3.96	35.3					6.09		.65
FAGA075	90488	71.6	72.8	1.2	100	4L41			1.40	3.54	20.2					4.94		.72
FAGA075	90489	72.8	73.9	1.1	100	4L41			2.43	5.40	35.3					7.83		.69
FAGA075	90490	75.1	75.9	.8	100	4L41			1.45	4.74	20.2					6.19		.77
FAGA075	90491	75.9	77.4	1.5	100	4L41			3.60	10.82	50.4					14.42		.75
FAGA075	90492	77.4	78.9	1.5	80	4L41			3.60	7.08	60.2					10.68		.66
FAGA075	90493	78.9	80.5	1.6	94	4L41			3.45	5.64	51.4					9.09		.62
FAGA075	90494	80.5	82.1	1.6	100	4A41			4.05	7.08	56.6					11.13		.64
FAGA075	90495	82.1	84.1	2.0	100	5D4a			.70	2.58	9.9					3.28		.79
FAGA075	90496	84.1	85.8	1.7	100	4A4			4.43	7.68	60.3					12.11		.63
FAGA075	90497	85.8	87.8	2.0	100	4A4			2.33	4.44	34.3					6.77		.66
FAGA075	90498	87.8	89.1	1.3	100	4L14			3.53	6.48	47.3					10.01		.65
FAGA075	90499	89.1	90.8	1.7	100	4L14			4.99	8.76	70.6					13.75		.64
FAGA075	90500	90.8	91.9	1.1	100	4L14			3.68	7.80	48.3					11.48		.68

DDH	SAMPLE	----DEPTHS----		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAO	PB+ZN	PC+PY	ZN	
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO	
FAGA075	9C501	92.3	93.9	1.6	100	4A4			1.63	3.60	24.3							5.23	.69
FAGA075	9C502	93.9	96.3	2.4	100	4A0			1.10	3.12	15.1							4.22	.74
FAGA075	9C503	96.3	97.8	1.5	100	4A4			2.25	7.08	34.3							9.33	.76
FAGA075	9C504	97.8	99.1	1.3	100	4D0			3.23	6.72	40.4							9.95	.68
FAGA075	9C505	99.1	100.3	1.2	100	4L14			3.98	6.60	52.4							10.58	.62
FAGA075	9C506	100.3	103.3	3.0	100	4A4			6.09	14.43	80.6							20.52	.70
FAGA075	9C507	103.3	104.7	1.4	100	4A43			3.23	8.97	53.5							12.20	.74
FAGA075	9C508	104.7	106.2	1.5	100	4A43			2.38	5.34	35.3							7.72	.69
FAGA075	9C509	106.2	107.7	1.5	100	4A43			4.95	6.36	59.3							11.31	.56
FAGA075	9C510	107.7	108.7	1.0	100	4A43			2.85	5.64	45.3							8.49	.66
FAGA075	9C511	109.1	110.9	1.8	100	4A4			3.08	5.88	40.4							8.96	.66
FAGA075	9C512	245.0	246.5	1.5	100	4E4			12.75	9.23	171.4							21.98	.42
FAGA075	9C513	249.0	250.6	1.6	100	4K4			6.68	5.16	78.5							11.84	.44
FAGA075	9C514	250.6	252.2	1.6	100	4AK			6.08	4.20	67.5							10.28	.41
FAGA075	9C515	253.0	253.6	.6	100	4AD			4.13	10.89	59.7							15.02	.73
FAGA075	9C516	253.6	254.7	1.1	100	4G4			3.90	7.44	57.6							11.34	.66
FAGA075	9C517	259.4	261.4	2.0	100	4G4			5.40	10.50	81.6							15.90	.66
FAGA075	9C518	261.4	262.5	1.1	100	4AG			4.50	8.23	67.5							12.73	.65
FAGA075	9C519	262.8	264.3	1.5	100	4G4			4.80	7.62	70.6							12.42	.61
FAGA075	9C520	264.3	264.9	.6	100	4G4			5.10	8.56	74.7							13.66	.63
FAGA008	9C521	72.7	74.7	2.0		4A0			.98	1.12	13.7							2.10	.53
FAGA008	9C522	74.7	76.2	1.5		4A0			.90	1.26	16.5							2.16	.58
FAGA008	9C523	76.2	80.2	4.0		4A0			.80	.90	11.0							1.70	.53
FAGA008	9C524	80.2	81.4	1.2		4A0			.21	.08	2.7							.29	.28
FAGA008	9C525	93.5	95.1	1.6		4D5			2.03	4.08	37.0							6.11	.67
FAGA008	9C526	95.1	95.3	.2		4D5			2.03	4.08	37.0							6.11	.67
FAGA008	9C527	95.3	96.9	1.6		4D5			2.48	4.62	31.5							7.10	.65
FAGA008	9C528	96.9	98.1	1.2		4D5			3.08	6.48	39.8							9.56	.68
FAGA008	9C529	177.9	180.6	2.7		4D5			3.23	6.11	50.7							9.34	.65
FAGA012	9C534	247.2	250.2	3.0		4C5		.04	2.00	2.70	30.9	.34						4.70	.57
FAGA012	9C536	250.2	253.3	3.1		4D5		.07	3.45	3.06	44.6	.34						6.51	.47
FAGA012	9C537	253.3	256.3	3.0		4D5		.05	2.35	3.48	38.4	.34						5.83	.60
FAGA020	9C538	183.8	185.0	1.2	100	5D4*		.04	.43	.70	11.0	.17						1.13	.62
FAGA020	9C539	185.0	186.8	1.8	100	4A4		.10	2.48	4.14	41.8	.69						6.62	.63
FAGA020	9C540	188.1	189.6	1.5	100	4A0		.04	1.73	3.06	28.1	.69						4.79	.64
FAGA020	9C541	189.6	191.1	1.5	100	4A4		.08	3.38	2.46	45.2	.69						5.84	.42
FAGA020	9C542	191.1	192.6	1.5	100	4A4		.04	2.50	3.54	56.2	.34						6.04	.59
FAGA020	9C543	192.6	194.2	1.6	94	4A4		.06	2.85	5.52	35.7	.34						8.37	.66
FAGA020	9C544	202.5	204.8	2.3	100	4A4		.14	2.42	3.16	37.9	.57						5.58	.57
FAGA020	9C545	204.8	206.0	1.2	100	4A4		.04	5.25	8.04	78.2	.69						13.29	.60
FAGA020	9C546	215.5	217.3	1.8	100	4A4		.23	4.79	6.68	87.8	.69						11.47	.58
FAGA020	9C547	217.3	218.8	1.5	100	4A4		.04	3.38	7.44	66.5	.69						10.82	.69
FAGA020	9C548	218.8	220.4	1.6	94	4A4		.06	2.85	6.72	50.1	.69						9.57	.70
FAGA020	9C549	220.4	221.9	1.5	100	4A4		.05	3.15	7.44	55.5	.69						10.59	.70
FAGA020	9C550	221.9	223.4	1.5	100	4A4		.04	2.43	5.40	45.9	.69						7.83	.69
FAGA020	9C551	223.4	224.9	1.5	100	4A4		.06	2.00	3.72	37.7	.69						5.72	.65
FAGA020	9C552	224.9	226.5	1.6	94	4A0		.06	.58	1.18	19.2	.34						1.76	.67
FAGA022	9C553	154.2	154.7	.5	100	4E80		.44	1.45	1.58	23.3	.34						3.03	.52
FAGA022	9C554	181.0	183.2	2.2	100	4E4		.13	5.03	5.52	68.6	.69						10.55	.52
FAGA022	9C555	183.2	184.8	1.6	94	4DL		.16	6.00	6.84	105.9	.69						12.84	.53

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAO	PB+ZN	PC+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGA022	90556	184.8	186.9	2.1	100	4L41		.13	.78	1.06	9.9	.17				1.84		.58
FAGA022	90557	186.9	188.7	1.8	100	4H2S		.24	.85	2.40	30.2	.17				3.25		.74
FAGA022	90558	229.9	231.0	1.1	100	4E4		.12	4.35	8.50	59.0	.69				12.85		.66
FAGA022	90559	231.0	232.1	1.1	64	4E4		.27	6.83	8.40	133.0	1.37				15.23		.55
FAGA022	90560	232.1	233.8	1.7	53	4E4		.15	3.23	4.44	50.7	.69				7.67		.58
FAGA022	90561	233.8	236.8	3.0	10	4A4		.09	5.33	8.88	78.2	.69				14.21		.62
FAGA022	90562	236.8	239.9	3.1	10	4A4		.07	2.35	5.16	48.0	.69				7.51		.69
FAGAG22	90563	239.9	242.6	2.7	100	4A4		.06	2.08	4.56	59.0	.69				6.64		.69
FAGAG22	90564	242.6	243.4	.8	25	4L12		.08	1.93	3.06	23.3	.34				4.99		.61
FAGAG22	90565	243.4	245.8	2.4	100	4L12		.08	.23	.43	5.5	.17				.66		.65
FAGAG22	90566	245.8	247.0	1.2	100	4A0		.12	.63	.25	20.6	.17				.88		.28
FAGAG22	90567	247.0	250.0	3.0	100	4A4		.10	3.83	6.96	52.1	.34				10.79		.65
FAGAG22	90568	250.0	251.3	1.3	100	4E0		.28	.69	1.40	16.5	.34				2.09		.67
FAGAG22	90569	251.3	252.6	1.3	92	4E0		.31	2.08	2.00	45.3	.69				4.08		.49
FAGAG22	90570	252.6	254.5	1.9	100	4A4		.12	4.35	8.16	62.4	.69				12.51		.65
FAGAG22	90571	254.5	257.4	2.9	100	4E4		.21	4.35	7.68	66.5	.69				12.03		.64
FAGAG22	90572	270.0	270.5	.5	100	4G4		.08	6.68	11.45	152.2	.69				18.13		.63
FAGAG22	90573	274.4	275.3	.9	100	4A0		.04	1.58	3.00	27.4	.69				4.58		.66
FAGAG22	90574	275.3	276.8	1.5	100	4D4		.08	6.60	12.67	94.6	.69				19.27		.66
FAGAG22	90575	276.8	278.8	2.0	100	4D4		.15	6.00	11.92	127.5	.69				17.92		.67
FAGAG22	90576	342.9	344.9	2.0	100	4EG4		.10	4.35	7.20	80.9	.69				11.55		.62
FAGAG22	90577	344.9	345.4	.5	60	4E4		.09	6.08	10.65	98.7	.69				16.73		.64
FAGAG22	90578	345.4	347.5	2.1	86	4A43		.04	3.53	6.36	43.9	.69				9.89		.64
FAGAG22	90579	347.5	349.2	1.7	94	4A43		.04	3.53	6.60	49.4	.69				10.13		.65
FAGAG22	90580	349.2	352.2	3.0	10	4G4		.10	4.88	7.80	100.1	.69				12.68		.62
FAGAG22	90581	352.2	354.8	2.6	100	4G4			5.18	8.76	88.8					13.94		.63
FAGAG22	90582	354.8	355.5	.7	86	5C4*			.50	.77	6.2					1.27		.61
FAGAG22	90583	355.5	356.3	.8	100	4G4			4.58	7.80	87.8					12.38		.63
FAGAG22	90584	356.3	356.7	.4	75	4G0			2.35	3.54	33.3					6.09		.58
FAGAG22	90585	361.1	362.3	1.2	100	4GL			3.08	5.28	64.5					8.36		.63
FAGAG22	90586	362.3	363.3	1.0	70	5B62			.14	.12	1.0					.26		.46
FAGU036	90587	15.2	16.8	1.6	100	4J0			8.17	10.82	133.0					18.99		.57
FAGU037	90588	10.1	10.7	.6	100	4E4			2.15	5.07	32.2					7.22		.70
FAGU037	90589	10.7	12.2	1.5	100	4E4			2.10	4.98	49.4					7.08		.70
FAGU037	90590	12.2	13.7	1.5	100	4EAG			2.60	5.68	47.3					8.28		.69
FAGU037	90591	13.7	15.2	1.5	40	4EG4			4.70	13.68	97.7					18.38		.74
FAGU037	90592	15.2	16.8	1.6	25	4E4			4.93	12.76	80.6					17.69		.72
FAGU037	90593	16.8	18.3	1.5	80	4E4			4.80	10.26	86.7					15.06		.68
FAGU037	90594	18.3	19.8	1.5	67	4E4			6.51	13.37	98.7					19.88		.67
FAGU037	90595	19.8	21.3	1.5	100	4E4			6.36	13.12	99.8					19.48		.67
FAGU037	90596	21.3	22.9	1.6	87	4E4			4.65	6.77	80.6					11.42		.59
FAGU037	90597	22.9	24.4	1.5	100	4A31			1.43	1.68	24.3					3.11		.54
FAGU037	90598	24.4	25.9	1.5	93	4A31			1.18	1.75	24.3					2.93		.60
FAGA111	90599	271.9	273.9	2.0	100	4CA0			.80	1.46	19.2					2.26		.65
FAGA111	90600	273.9	275.4	1.5	100	4CA0			.85	1.14	8.9					1.99		.57
FAGA111	90601	275.4	276.2	.8	100	4CA0			1.03	1.72	12.0					2.75		.63
FAGA111	90602	277.8	279.8	2.0	100	4CA0			1.00	1.10	15.1					2.10		.52
FAGA111	90603	279.8	281.0	1.2	100	4ACO			.78	.96	14.1					1.74		.55
FAGA111	90604	281.0	282.1	1.1	100	4ACO			.88	1.12	13.0					2.00		.56
FAGA131	90605	115.2	117.0	1.8	17	4A4			2.95	4.60	33.3					7.55		.61

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAO	PB+ZN	PO+PY	ZN
		FROM	TO	M.	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGA131	90606	117.0	118.9	1.9	47	4A4			4.50	8.70	75.8					13.20		.66
FAGU185	90607	6.1	7.6	1.5	87	4A0			1.23	1.85	20.2					3.08		.60
FAGU185	90608	7.6	9.1	1.5	87	4A34			6.43	14.02	93.9					20.45		.69
FAGU185	90609	9.1	10.7	1.6	100	4A34			6.83	15.27	110.1					22.10		.69
FAGU185	90610	10.7	12.2	1.5	100	4DE4			5.86	11.84	66.5					17.70		.67
FAGU185	90611	12.2	13.7	1.5	100	4E4			7.81	15.99	84.7					23.80		.67
FAGU185	90612	13.7	15.2	1.5	100	4E4			6.43	11.59	84.7					18.02		.64
FAGU185	90613	15.2	16.8	1.6	100	4E4			8.11	17.43	104.9					25.54		.68
FAGU185	90614	16.8	18.3	1.5	100	4D4			10.47	26.45	172.5					36.92		.72
FAGU185	90615	18.3	19.8	1.5	100	4D34			6.23	17.52	90.9					23.75		.74
FAGU185	90616	19.8	20.5	.7	100	4D34			9.69	20.65	141.3					30.34		.68
FAGU185	90617	57.9	58.6	.7	100	4E46			5.50	9.70	80.6					15.20		.64
FAGU191	90618	6.1	9.1	3.0	77	4A13			.45	.80	9.9					1.25		.64
FAGU191	90619	9.1	12.2	3.1	97	4A13			.60	1.30	25.4					1.90		.68
FAGU191	90620	12.2	13.7	1.5	93	4A13			3.35	3.75	50.4					7.10		.53
FAGU191	90621	13.7	15.2	1.5	100	4DE4			7.15	12.83	94.6					19.98		.64
FAGU191	90622	15.2	16.8	1.6	100	4EA			5.00	9.60	83.7					14.60		.66
FAGU191	90623	16.8	18.3	1.5	93	4E4			6.62	12.28	86.7					18.90		.65
FAGU191	90624	18.3	19.8	1.5	73	4ED4			6.85	13.69	103.9					20.54		.67
FAGU191	90625	19.8	21.3	1.5	73	4D45			8.96	14.71	126.2					23.67		.62
FAGU191	90626	21.3	24.3	3.0	57	4DE4			6.95	12.53	109.0					19.48		.64
FAGU191	90627	50.3	53.3	3.0	40	4E4			5.33	15.46	75.8					20.79		.74
FAGU191	90628	53.3	56.4	3.1	35	4EC			4.40	13.20	67.5					17.60		.75
FAGU191	90629	56.4	57.9	1.5	60	4E4			7.05	16.45	114.2					23.50		.70
FAGU193	90630	36.5	38.1	1.6	100	4EG4			7.55	10.60	100.8					18.15		.58
FAGU193	90631	38.1	39.6	1.5	100	4G4			4.10	9.75	50.4					13.85		.70
FAGU193	90632	39.6	41.1	1.5	93	4GA4			6.55	10.21	78.9					16.76		.61
FAGU193	90633	41.1	42.7	1.6	100	4A4			6.25	9.20	98.7					15.45		.60
FAGU195	90634	16.8	18.3	1.5	80	4E4			3.95	10.08	57.6					14.03		.72
FAGU195	90635	18.3	19.8	1.5	93	4E4			4.33	11.32	59.3					15.65		.72
FAGU195	90636	19.8	21.3	1.5	93	4E4			5.80	12.98	91.9					18.78		.69
FAGU195	90637	21.3	22.9	1.6	94	4E4			6.92	15.01	108.0					21.93		.68
FAGU195	90638	22.9	24.4	1.5	100	4E4			3.40	7.80	50.4					11.20		.70
FAGU195	90639	24.4	25.9	1.5	87	4D4			7.67	14.91	114.9					22.58		.66
FAGU195	90640	25.9	27.4	1.5	100	4E4			7.94	17.86	114.9					25.80		.69
FAGU195	90641	27.4	29.0	1.6	63	4E4			6.95	14.29	96.7					21.24		.67
FAGU195	90642	29.0	30.5	1.5	80	4A13			6.15	7.99	84.7					14.14		.57
FAGU195	90643	30.5	33.5	3.0	33	4A13			.05	.13	6.2					.18		.72
FAGU196	90644	.0	3.0	3.0	53	4A0			1.80	1.70	20.2					3.50		.49
FAGU196	90645	3.0	4.5	1.5	93	4A0			1.95	2.93	26.4					4.88		.60
FAGU196	90646	4.5	6.0	1.5	87	4A0			1.63	1.63	22.3					3.26		.50
FAGU196	90647	6.0	7.5	1.5	100	4C0			1.60	.88	22.3					2.48		.35
FAGU196	90648	7.5	9.0	1.5	93	4C0			.88	.35	12.0					1.23		.28
FAGU196	90649	9.0	10.5	1.5	87	4A0			2.20	2.00	32.2					4.20		.48
FAGU196	90650	10.5	12.0	1.5	87	4A4			2.88	2.55	36.3					5.43		.47
FAGU196	90651	12.0	13.5	1.5	87	4A4			2.70	2.95	32.2					5.65		.52
FAGU196	90652	13.5	15.0	1.5	80	4A0			2.80	1.25	30.2					4.05		.31
FAGU196	90653	15.0	16.5	1.5	100	4A0			3.10	1.85	31.2					4.95		.37
FAGU196	90654	16.5	18.0	1.5	87	4A0			2.70	.80	26.4					3.50		.23
FAGU196	90655	18.0	19.5	1.5	100	4A0			.13	.55	3.1					.68		.81

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAO	PB+ZN	PO+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGU196	90656	19.5	21.0	1.5	100	4A0			.10	.10	6.2					.20		.50
FAGU196	90657	21.0	22.5	1.5	100	4A0			.14	.35	6.2					.49		.71
FAGU196	90658	22.5	25.5	3.0	90	4A0			.75	.73	8.9					1.48		.49
FAGU196	90659	25.5	28.5	3.0	93	4A0			.18	.40	3.1					.58		.69
FAGU196	90660	28.5	31.5	3.0	93	4A0			.13	.93	3.1					1.06		.88
FAGU196	90661	31.5	34.5	3.0	100	4A0			.53	1.23	8.9					1.76		.70
FAGU196	90662	34.5	36.6	2.1	95	4A4			1.95	3.40	30.2					5.35		.64
FAGU196	90663	36.6	38.1	1.5	100	4AE			2.58	4.15	41.5					6.73		.62
FAGU196	90664	38.1	39.6	1.5	100	4E4			6.23	8.77	92.9					15.00		.58
FAGU196	90665	39.6	40.3	.7	100	4E4			6.10	8.47	102.9					14.57		.58
FAGU196	90666	62.5	64.0	1.5	100	4EG			5.00	8.21	93.9					13.21		.62
FAGU196	90667	64.0	65.5	1.5	100	4EG			6.85	5.10	184.5					11.95		.43
FAGU196	90668	65.5	67.0	1.5	100	4G4			5.70	8.06	108.0					13.76		.59
FAGU196	90669	67.0	68.5	1.5	100	4EG			4.00	6.80	69.6					10.80		.63
FAGU196	90670	68.5	70.0	1.5	100	4EG4			5.00	8.49	82.6					13.49		.63
FAGU196	90671	70.0	71.5	1.5	100	4EG4			4.35	7.50	76.8					11.85		.63
FAGU196	90672	94.5	96.0	1.5	33	4J4			4.28	19.19	61.4					23.47		.82
FAGU196	90673	96.0	97.5	1.5	80	4J4			9.02	20.34	150.2					29.36		.69
FAGU196	90674	97.5	99.0	1.5	87	3G0			2.53	5.65	42.5					8.18		.69
FAGU196	90675	99.0	100.5	1.5	87	4E4			2.03	4.55	36.3					6.58		.69
FAGU196	90676	100.5	102.0	1.5	87	4E4			4.65	8.31	70.6					12.96		.64
FAGU196	90677	102.0	103.5	1.5	80	4E10			1.05	3.68	25.4					4.73		.78
FAGU196	90678	103.5	105.0	1.5	93	4E4			2.23	3.15	39.4					5.38		.59
FAGU196	90679	105.0	106.5	1.5	87	4E4			1.63	4.03	30.2					5.66		.71
FAGU196	90680	106.5	108.0	1.5	73	4C0			1.20	3.18	25.4					4.38		.73
FAGU196	90681	108.0	109.5	1.5	60	4D0			2.58	2.75	45.3					5.33		.52
FAGU196	90682	109.5	111.0	1.5	33	4D0			3.25	4.85	48.3					8.10		.60
FAGU189	90683	56.4	58.4	2.0	90	4E4			2.65	5.40	32.2					8.05		.67
FAGU189	90684	58.4	60.4	2.0	65	4A10			1.18	3.40	21.3					4.58		.74
FAGU189	90685	60.4	61.0	.6	100	4E0			1.05	1.80	25.4					2.85		.63
FAGU189	90686	61.0	62.5	1.5	100	5D4\$			.18	1.10	3.1					1.28		.86
FAGU189	90687	82.9	85.3	2.4	100	4E0			3.20	1.80	29.1					5.00		.36
FAGU189	90688	85.3	87.5	2.2	91	4E0			1.08	.85	16.1					1.93		.44
FAGU189	90689	87.5	88.4	.9	89	4E0			.55	.90	14.1					1.45		.62
FAGU189	90690	88.4	89.9	1.5	100	4E0			1.03	1.43	18.2					2.46		.58
FAGU189	90691	89.9	90.8	.9	78	4E0			1.25	1.23	17.1					2.48		.50
FAGU189	90692	90.8	93.0	2.2	86	4EC			1.85	2.15	27.4					4.00		.54
FAGU189	90693	93.0	93.9	.9	22	4C0			1.05	1.43	12.0					2.48		.58
FAGU189	90694	93.9	95.4	1.5	100	4C0			.40	.38	8.2					.78		.49
FAGU189	90695	95.4	96.3	.9	56	4C0			.53	.85	5.1					1.38		.62
FAGU189	90696	96.3	97.8	1.5	100	4C0			.55	.98	6.2					1.53		.64
FAGU189	90697	97.8	100.3	2.5	64	4C0			2.78	2.13	24.3					4.91		.43
FAGU189	90698	100.3	101.8	1.5	93	4D0			3.68	2.03	32.2					5.71		.36
FAGU189	90699	101.8	103.6	1.8	94	4C0			1.85	1.20	20.2					3.05		.39
FAGU189	90700	103.6	105.2	1.6	100	4D0			2.48	2.63	29.1					5.11		.51
FAGU189	90701	105.2	106.7	1.5	100	4D0			4.45	4.95	67.5					9.40		.53
FAGU189	90702	106.7	108.2	1.5	100	4C0			1.53	1.13	25.4					2.66		.42
FAGU189	90703	108.2	109.7	1.5	100	4EC			1.03	.83	15.1					1.86		.45
FAGU189	90704	112.8	114.3	1.5	100	4C0			2.03	2.65	36.3					4.68		.57
FAGU198	90705	45.7	47.2	1.5	100	4BE			2.20	1.15	39.4					3.35		.34

DDH	SAMPLE	-----DEPTHS----	INT	REC	ROCK	S.G.	CU	PS	ZN	AG	AU	PO	PY	BAO	PB+ZN	PC+PY	ZN
		FROM TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGU198	90706	47.2	49.0	1.8	100	4E0		2.88	1.85	42.5					4.73		.39
FAGU198	90707	90.5	92.0	1.5	100	4E46		5.76	8.04	101.8					13.80		.58
FAGU198	90708	92.0	93.5	1.5	100	4E46		6.65	9.70	123.1					16.35		.59
FAGU198	90709	93.5	94.7	1.2	100	4E46		5.44	9.70	91.9					15.14		.64
FAGU198	90710	134.1	135.6	1.5	100	4EA4		2.88	2.85	36.3					5.73		.50
FAGU198	90711	135.6	137.1	1.5	100	4A1		.88	.88	13.0					1.76		.50
FAGU198	90712	137.1	138.6	1.5	100	4A1		.08	.10	4.1					.18		.56
FAGU198	90713	146.9	148.4	1.5	100	4A1		1.28	1.50	20.2					2.78		.54
FAGU198	90714	148.4	149.9	1.5	87	4A1		.18	.70	7.2					.88		.80
FAGU198	90715	149.9	151.4	1.5	100	4A1		1.18	1.33	23.3					2.51		.53
FAGU199	90716	2.1	3.6	1.5	60	4E4		8.39	12.65	124.1					21.04		.60
FAGU199	90717	3.6	5.1	1.5	87	4EG4		7.40	10.21	114.2					17.61		.58
FAGU199	90718	5.1	6.6	1.5	93	4G4		6.40	8.85	92.9					15.25		.58
FAGU199	90719	6.6	8.1	1.5	100	4G4		7.85	10.31	113.1					18.16		.57
FAGU199	90720	8.1	9.6	1.5	80	4G4		6.50	8.95	75.8					15.45		.58
FAGU199	90721	9.6	11.1	1.5	67	4G4		6.75	10.15	76.8					16.90		.60
FAGU199	90722	11.1	12.6	1.5	67	4E4		6.97	8.69	104.9					15.66		.55
FAGU199	90723	12.6	14.1	1.5	67	5C4*		3.60	8.16	46.3					11.76		.69
FAGU199	90724	14.1	15.6	1.5	53	4A10		3.03	3.35	47.3					6.38		.53
FAGU199	90725	15.6	17.1	1.5	87	4AE4		6.75	6.52	97.7					13.27		.49
FAGU199	90726	17.1	18.6	1.5	93	4G4		8.60	11.52	156.3					20.12		.57
FAGU199	90727	18.6	20.1	1.5	80	4G4		7.40	9.93	114.2					17.33		.57
FAGU199	90728	20.1	21.6	1.5	93	4G4		7.00	9.70	93.9					16.70		.58
FAGU199	90729	21.6	23.1	1.5	60	4G4		7.20	9.65	101.8					16.85		.57
FAGU199	90730	23.1	24.6	1.5	53	4G4		4.18	6.31	79.5					10.49		.60
FAGU199	90731	27.0	28.5	1.5	100	4G4		6.10	10.21	108.0					16.31		.63
FAGU199	90732	28.5	30.0	1.5	93	4G4		5.40	9.55	98.7					14.95		.64
FAGU199	90733	30.0	31.5	1.5	100	4G4		6.20	9.85	139.2					16.05		.61
FAGU199	90734	31.5	33.0	1.5	100	4G4		6.40	9.25	104.9					15.65		.59
FAGU199	90735	33.0	34.5	1.5	87	4G4		5.10	9.78	85.7					14.88		.66
FAGU199	90736	34.5	36.0	1.5	73	4EG4		4.55	9.18	62.4					13.73		.67
FAGU199	90737	103.0	104.5	1.5	93	4E4		3.90	3.65	49.4					7.55		.48
FAGU199	90738	104.5	106.0	1.5	100	4E0		1.83	1.05	29.1					2.88		.36
FAGU199	90739	106.0	107.5	1.5	73	4K0		1.13	.30	27.4					1.43		.21
FAGU199	90740	107.5	109.0	1.5	100	4E4		6.80	6.47	68.6					13.27		.49
FAGU199	90741	109.0	110.5	1.5	87	4E0		1.95	1.73	23.3					3.68		.47
FAGU200	90742	6.0	7.9	1.9	63	4E4		7.95	15.80	126.2					23.75		.67
FAGU200	90743	7.9	9.4	1.5	73	4E4		9.17	16.40	138.2					25.57		.64
FAGU200	90744	9.4	10.9	1.5	60	4E4		8.88	14.23	122.1					23.11		.62
FAGU200	90745	10.9	12.4	1.5	87	4E4		9.94	11.45	147.1					21.39		.54
FAGU200	90746	12.4	13.9	1.5	60	4E4		6.30	10.43	100.8					16.73		.62
FAGU200	90747	13.9	15.4	1.5	60	5A6		.88	2.38	16.1					3.26		.73
FAGU200	90748	15.4	16.9	1.5	73	4E4		6.63	11.55	110.1					18.18		.64
FAGU200	90749	16.9	18.4	1.5	67	4E4		9.52	15.70	162.5					25.22		.62
FAGU200	90750	18.4	20.0	1.6	63	4E4		8.63	14.68	117.3					23.31		.63
FAGU200	90751	21.3	22.9	1.6	94	4A0		2.33	1.10	31.2					3.43		.32
FAGU200	90752	22.9	24.4	1.5	100	4A4		2.50	4.30	43.5					6.80		.63
FAGU200	90753	24.4	27.0	2.6	54	4A4		2.05	3.45	30.2					5.50		.63
FAGU204	90754	19.8	21.3	1.5	87	4E4		7.32	12.90	102.9					20.22		.64
FAGU204	90755	21.3	22.9	1.6	75	4E4		6.48	13.51	89.8					19.99		.68

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAO	PB+ZN	PC+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGU204	90756	22.9	24.4	1.5	100	4EK4			2.33	8.26	59.3					10.59		.78
FAGU204	90757	24.4	25.9	1.5	60	4E4			3.45	9.60	49.0					13.05		.74
FAGU204	90758	25.9	27.4	1.5	93	4E4			5.51	9.37	72.7					14.88		.63
FAGU204	90759	27.4	29.0	1.6	88	4E4			11.45	17.33	150.2					28.78		.60
FAGU204	90760	29.0	30.7	1.7	94	4E4			7.25	10.67	114.2					17.92		.60
FAGU204	90761	30.7	32.2	1.5	87	4A1			1.60	2.90	26.4					4.50		.64
FAGU207	90762	.0	4.6	4.6	33	4A43			4.80	8.78	82.6					13.58		.65
FAGU207	90763	4.6	6.1	1.5	93	4A43			4.10	7.87	63.4					11.97		.66
FAGU207	90764	7.6	9.1	1.5	80	4A43			3.00	6.67	59.3					9.67		.69
FAGU207	90765	9.1	10.6	1.5	100	4A43			2.15	4.00	38.4					6.15		.65
FAGU207	90766	10.6	12.1	1.5	100	4A43			3.10	4.56	54.5					7.66		.60
FAGU207	90767	12.1	13.6	1.5	100	4A43			2.95	5.56	52.5					8.51		.65
FAGU207	90768	13.6	15.1	1.5	80	4A43			3.00	5.00	45.3					8.00		.63
FAGU207	90769	15.1	16.7	1.6	62	4A43			2.90	7.98	43.5					10.88		.73
FAGU207	90770	16.7	18.2	1.5	67	4A43			2.68	3.90	35.3					6.58		.59
FAGU207	90771	18.2	20.4	2.2	95	4A43			3.90	8.48	59.3					12.38		.69
FAGU215	90772	4.2	6.0	1.8	39	4A34			2.95	6.14	53.5					9.09		.68
FAGU215	90773	7.8	9.3	1.5	93	4AL			1.28	2.10	23.3					3.38		.62
FAGU215	90774	9.3	10.8	1.5	100	4AC			1.58	2.33	25.4					3.91		.60
FAGU215	90775	10.8	12.0	1.2	100	4ACL			1.33	2.70	25.4					4.03		.67
FAGU215	90776	65.5	67.1	1.6	62	4G4			5.99	9.17	84.7					15.16		.60
FAGU215	90777	67.1	68.6	1.5	80	4A4			5.10	9.25	86.7					14.35		.64
FAGU215	90778	68.6	70.1	1.5	80	4AL			3.63	6.14	59.3					9.77		.63
FAGU215	90779	100.6	103.6	3.0	100	4A1			.05	.18	2.1					.23		.78
FAGU215	90780	103.6	106.7	3.1	84	4A1			.05	.38	3.1					.43		.88
FAGU215	90781	117.3	118.8	1.5	100	4A4			2.23	4.00	38.4					6.23		.64
FAGU215	90782	118.8	120.4	1.6	94	4A0			1.55	2.93	20.2					4.48		.65
FAGU215	90783	129.5	131.1	1.6	12	4E4			5.96	4.07	71.7					10.03		.41
FAGU215	90784	131.1	132.6	1.5	13	4L0			2.43	2.60	32.2					5.03		.52
FAGU216	90785	.0	1.5	1.5	27	4A34			3.88	5.57	65.5					9.45		.59
FAGU216	90786	1.5	3.0	1.5	100	4A34			1.90	4.30	37.4					6.20		.69
FAGU216	90787	3.0	4.6	1.6	100	4A34			2.93	6.17	56.6					9.10		.68
FAGU216	90788	4.6	6.1	1.5	100	4A34			3.95	7.21	70.6					11.16		.65
FAGU216	90789	6.1	7.6	1.5	100	4A34			5.00	10.06	80.6					15.06		.67
FAGU216	90790	7.6	9.1	1.5	100	4A34			2.58	5.46	41.5					8.04		.68
FAGU216	90791	9.1	10.7	1.6	100	4A34			2.75	6.70	45.3					9.45		.71
FAGU216	90792	10.7	12.5	1.8	94	4A34			1.48	4.38	26.4					5.86		.75
FAGU216	90793	35.1	36.6	1.5	100	4E4			9.57	19.93	138.2					29.50		.68
FAGU216	90794	36.6	38.1	1.5	100	4E4			13.40	21.48	215.7					34.88		.62
FAGU216	90795	38.1	39.6	1.5	100	4E4			10.43	18.62	191.7					29.05		.64
FAGU216	90796	46.1	48.1	2.0	100	4D4			5.55	9.52	96.7					15.07		.63
FAGU216	90797	49.8	51.8	2.0	100	4D0			3.78	3.75	50.4					7.53		.50
FAGU216	90798	51.8	53.3	1.5	100	4A3			1.05	1.35	17.1					2.40		.56
FAGU192	90799	.0	1.9	1.9	58	4A4			2.13	4.10	27.4					6.23		.66
FAGU192	90800	1.9	3.8	1.9	89	4A4			2.93	2.70	35.3					5.63		.48
FAGU192	90801	3.8	5.3	1.5	93	4C0			.85	1.18	9.9					2.03		.58
FAGU192	90802	5.3	6.8	1.5	100	4C0			1.93	2.50	22.3					4.43		.56
FAGU192	90803	6.8	8.3	1.5	100	4C0			1.10	1.05	13.0					2.15		.49
FAGU192	90804	8.3	9.8	1.5	100	4C0			.95	1.43	9.9					2.38		.60
FAGU192	90805	9.8	12.8	3.0	100	4C0			1.03	1.48	13.0					2.51		.59

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAO	PB+ZN	PC+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGU192	90806	15.0	16.5	1.5	93	4D0			2.48	3.25	35.3					5.73		.57
FAGU192	90807	16.5	18.0	1.5	100	4C0			1.93	2.80	22.3					4.73		.59
FAGU192	90808	18.0	19.5	1.5	100	4C0			1.50	2.00	17.1					3.50		.57
FAGU192	90809	19.5	21.0	1.5		4C0			2.05	2.93	24.3					4.98		.59
FAGU192	90810	21.0	22.5	1.5	100	4C0			2.08	2.85	25.4					4.93		.58
FAGU192	90811	60.7	63.7	3.0	93	4A0			.35	.83	8.9					1.18		.70
FAGU192	90812	63.7	66.7	3.0	87	4A0			1.38	2.20	22.3					3.58		.61
FAGU192	90813	66.7	69.0	2.3	87	4A0			.03	.43	7.2					.46		.94
FAGU192	90814	69.0	70.5	1.5	100	4E4			3.93	5.25	65.5					9.18		.57
FAGU192	90815	70.5	72.0	1.5	100	4EG4			3.18	7.78	57.6					10.96		.71
FAGU192	90816	72.0	73.5	1.5	100	4E46			4.50	8.24	65.5					12.74		.65
FAGU192	90817	73.5	75.0	1.5	100	4E46			2.63	4.60	33.3					7.23		.64
FAGU192	90818	75.0	76.5	1.5	100	4E60			1.13	3.18	17.1					4.31		.74
FAGU192	90819	76.5	78.0	1.5	100	4EG0			1.10	2.93	12.0					4.03		.73
FAGU192	90820	78.0	79.5	1.5	100	4EG			3.23	6.01	50.4					9.24		.65
FAGU192	90821	79.5	81.0	1.5	100	4EG4			5.85	11.16	85.7					17.01		.66
FAGU192	90822	81.0	82.5	1.5	100	4E4			4.65	3.35	50.4					8.00		.42
FAGU192	90823	82.5	84.0	1.5	100	4E0			2.20	1.75	29.1					3.95		.44
FAGU192	90824	84.0	85.5	1.5	100	4E4			3.28	4.40	51.4					7.68		.57
FAGU192	90825	85.5	87.0	1.5	80	4E4			4.08	6.25	62.4					10.33		.61
FAGU192	90826	87.0	88.5	1.5	87	4L4			1.05	2.13	15.1					3.18		.67
FAGU192	90827	88.5	90.0	1.5	100	4E46			4.78	7.17	62.4					11.95		.60
FAGU192	90828	90.0	91.5	1.5	93	4E46			3.90	7.88	60.3					11.78		.67
FAGU192	90829	91.5	93.0	1.5	87	4A0			.88	1.30	16.1					2.18		.60
FAGU192	90830	93.0	94.5	1.5	100	4E4			4.05	7.73	60.3					11.78		.66
FAGU192	90831	94.5	96.0	1.5	100	4A4			3.00	4.60	44.2					7.60		.61
FAGU192	90832	96.0	97.5	1.5	100	4EA4			2.75	5.56	40.5					8.31		.67
FAGU192	90833	97.5	99.0	1.5	100	4A0			.93	1.43	29.1					2.36		.61
FAGU192	90834	99.0	100.5	1.5	100	4AG			3.00	6.54	51.4					9.54		.69
FAGU192	90835	100.5	102.0	1.5	100	4A34			4.03	7.42	62.4					11.45		.65
FAGU192	90836	102.0	103.5	1.5	100	4A4			2.05	3.68	32.2					5.73		.64
FAGU192	90837	103.5	105.0	1.5	100	4A4			4.70	4.70	61.4					9.40		.50
FAGU192	90838	105.0	106.5	1.5	100	4A31			.45	.33	16.1					.78		.42
FAGU192	90839	106.5	108.0	1.5	100	4AC3			.08	1.38	8.2					1.46		.95
FAGU192	90840	108.0	109.5	1.5	100	4A1			.13	1.15	11.0					1.28		.90
FAGU192	90841	109.5	111.0	1.5	100	4A1			.10	.30	9.9					.40		.75
FAGU192	90842	111.0	112.5	1.5	100	4A1			.08	.25	13.0					.33		.76
FAGU192	90843	112.5	114.0	1.5	100	4A1			.08	.53	12.0					.61		.87
FAGU192	90844	114.0	115.5	1.5	100	4C30			.15	1.03	12.0					1.18		.87
FAGU192	90845	115.5	117.3	1.8	83	4C30			.43	1.30	16.1					1.73		.75
FAGU194	90846	1.2	4.0	2.8	82	4A4			2.35	3.00	28.5					5.35		.56
FAGU194	90847	4.0	5.5	1.5	100	4C0			1.55	.93	19.2					2.48		.38
FAGU194	90848	5.5	7.0	1.5	93	4C0			1.03	1.40	11.0					2.43		.58
FAGU194	90849	7.0	8.5	1.5	100	4D0			1.98	3.10	27.4					5.08		.61
FAGU194	90850	8.5	10.0	1.5	100	4C0			.90	1.80	9.9					2.70		.67
FAGU194	90851	10.0	11.5	1.5	93	4C0			1.28	1.60	12.0					2.88		.56
FAGU194	90852	11.5	13.0	1.5	100	4C0			.93	1.30	8.9					2.23		.58
FAGU194	90853	13.0	14.5	1.5	87	4C0			.95	.63	11.0					1.58		.40
FAGU194	90854	14.5	17.5	3.0	90	4A0			2.33	2.55	33.3					4.88		.52
FAGU194	90855	17.5	19.8	2.3	100	4A0			2.05	2.75	28.5					4.80		.57

DDH	SAMPLE	---DEPTHS---	INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAO	PB+ZN	PO+PY	ZN
		FROM TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGU194	90856	39.5	41.0	1.5	100	4A0		.40	1.00	8.2					1.40		.71
FAGU194	90857	41.0	42.5	1.5	93	4A0		1.08	2.28	20.2					3.36		.68
FAGU194	90858	42.5	44.0	1.5	93	4A0		.53	1.13	12.0					1.66		.68
FAGU194	90859	44.0	45.5	1.5	100	4A0		.23	.78	6.2					1.01		.77
FAGU194	90860	45.5	47.0	1.5	100	4A00		.23	.73	7.2					.96		.76
FAGU194	90861	47.0	48.5	1.5	100	4A0		.13	.43	7.2					.56		.77
FAGU194	90862	48.5	50.0	1.5	87	4A13		1.90	3.90	34.3					5.80		.67
FAGU194	90863	50.0	51.5	1.5	100	4A13		3.65	7.20	68.6					10.85		.66
FAGU194	90864	51.5	53.4	1.9	89	4EC		3.23	5.82	59.3					9.05		.64
FAGU194	90865	57.2	58.7	1.5	93	4C83		3.00	4.25	58.6					7.25		.59
FAGU194	90866	58.7	60.2	1.5	100	4E4		8.97	11.07	114.9					20.04		.55
FAGU194	90867	60.2	61.7	1.5	87	4G4		4.23	7.93	96.7					12.16		.65
FAGU194	90868	61.7	63.2	1.5	93	4Q*		3.28	5.48	58.6					8.76		.63
FAGU194	90869	63.2	64.7	1.5	100	4EG		3.38	5.71	48.3					9.09		.63
FAGU194	90870	64.7	66.2	1.5	100	4E4		4.90	6.57	81.6					11.47		.57
FAGU194	90871	66.2	67.7	1.5	93	4EG		3.20	6.90	80.6					10.10		.68
FAGU194	90872	67.7	69.2	1.5	93	4E4		4.13	9.21	74.7					13.34		.69
FAGU194	90873	69.2	70.7	1.5	87	4E4		5.00	8.26	84.7					13.26		.62
FAGU194	90874	70.7	72.2	1.5	100	4E4		3.93	4.00	57.6					7.93		.50
FAGU194	90875	72.2	73.7	1.5	80	4E0		2.70	1.50	43.5					4.20		.36
FAGU194	90876	73.7	75.2	1.5	100	4E4		4.94	5.91	78.9					10.85		.54
FAGU194	90877	75.2	76.2	1.0	100	4E4		3.90	5.05	78.9					8.95		.56
FAGU194	90878	87.2	88.7	1.5	100	4A4		9.71	18.19	147.1					27.90		.65
FAGU194	90879	88.7	90.2	1.5	100	4E14		6.99	14.00	104.9					20.99		.67
FAGU194	90880	90.2	91.7	1.5	100	4E14		5.23	8.04	79.5					13.27		.61
FAGU194	90881	91.7	93.2	1.5	100	4EC		2.73	5.05	43.5					7.78		.65
FAGU194	90882	93.2	94.7	1.5	100	4C3		.55	1.05	15.1					1.60		.66
FAGU194	90883	94.7	96.2	1.5	100	4C3		.88	1.93	17.1					2.81		.69
FAGU194	90884	96.2	97.7	1.5	100	4D3		4.25	6.19	63.4					10.44		.59
FAGU194	90885	97.7	99.2	1.5	100	4C3		1.00	2.48	21.3					3.48		.71
FAGU194	90886	99.2	100.7	1.5	100	4C3		1.43	2.98	26.4					4.41		.68
FAGU194	90887	100.7	102.2	1.5	100	4C35		1.05	1.28	25.4					2.33		.55
FAGU194	90888	102.2	103.7	1.5	100	4C35		.13	.65	18.2					.78		.83
FAGU194	90889	103.7	105.2	1.5	100	4C3		.48	.50	18.2					.98		.51
FAGU194	90890	105.2	106.7	1.5	100	4D3		2.28	2.80	37.4					5.08		.55
FAGU194	90891	106.7	108.2	1.5	100	4D3		3.88	5.00	60.3					8.88		.56
FAGU194	90892	108.2	109.7	1.5	100	4C3		.70	1.63	25.4					2.33		.70
FAGU194	90893	109.7	111.4	1.7	88	4C3		2.08	1.93	34.3					4.01		.48
FAGU206	90894	1.5	3.0	1.5	93	4A4		4.35	8.98	66.5					13.33		.67
FAGU206	90895	3.0	4.6	1.6	87	4A34		3.45	4.60	45.3					8.05		.57
FAGU206	90896	4.6	6.1	1.5	100	4A34		5.70	4.00	67.5					9.70		.41
FAGU206	90897	6.1	7.6	1.5	87	4D54		9.75	6.33	114.2					16.08		.39
FAGU206	90898	7.6	9.1	1.5	93	4D5		4.78	4.25	58.6					9.03		.47
FAGU206	90899	9.1	12.2	3.1	100	4D5		3.65	4.20	43.5					7.85		.54
FAGU206	90900	12.2	13.7	1.5	100	4A43		6.50	2.50	69.6					9.00		.28
FAGU206	90901	13.7	15.2	1.5	100	4A43		8.50	4.40	89.8					12.90		.34
FAGU206	90902	15.2	16.8	1.6	94	4A43		4.03	2.03	46.3					6.06		.33
FAGU206	90903	16.8	18.3	1.5	100	4A43		5.04	2.33	55.5					7.37		.32
FAGU206	90904	18.3	19.8	1.5	100	4A43		4.85	1.63	55.5					6.48		.25
FAGU206	90905	19.8	21.3	1.5	100	4A43		5.70	1.48	64.5					7.18		.21

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAO	PB+ZN	PO+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGU206	90906	21.3	22.9	1.6	100	4A34			8.55	7.52	83.7					16.07		.47
FAGU206	90907	22.9	24.4	1.5	100	4A34			3.70	2.70	41.5					6.40		.42
FAGU206	90908	24.4	25.9	1.5	100	4A34			3.33	4.10	47.3					7.43		.55
FAGU206	90909	25.9	27.4	1.5	80	4D0			2.15	4.66	37.4					6.81		.68
FAGU206	90910	27.4	29.0	1.6	94	4D0			2.38	5.00	44.2					7.38		.68
FAGU206	90911	29.0	30.5	1.5	93	4A4			2.15	4.76	40.5					6.91		.69
FAGU206	90912	30.5	32.0	1.5	100	4A4			1.90	3.95	39.4					5.85		.68
FAGU206	90913	32.0	33.5	1.5	100	4A4			1.60	3.73	33.3					5.33		.70
FAGU206	90914	33.5	35.1	1.6	100	4A4			1.90	4.68	39.4					6.58		.71
FAGU206	90915	35.1	36.6	1.5	100	4A0			1.75	2.53	31.2					4.28		.59
FAGU206	90916	36.6	38.1	1.5	100	4A4			3.35	6.48	57.6					9.83		.66
FAGU206	90917	38.1	39.6	1.5	100	4A4			2.48	4.06	46.3					6.54		.62
FAGU206	90918	39.6	41.1	1.5	100	4A4			3.30	7.44	66.5					10.74		.69
FAGU206	90919	41.1	42.7	1.6	94	4D5			1.80	3.30	29.1					5.10		.65
FAGU206	90920	42.7	44.2	1.5	100	4C5			1.15	1.40	15.1					2.55		.55
FAGU206	90921	44.2	45.7	1.5	100	4C5			1.40	2.88	23.3					4.28		.67
FAGU206	90922	45.7	47.2	1.5	100	4A0			1.38	3.25	26.4					4.63		.70
FAGU206	90923	47.2	48.8	1.6	100	4A4			1.68	4.18	30.2					5.86		.71
FAGU206	90924	48.8	50.3	1.5	93	4A0			1.43	3.18	21.3					4.61		.69
FAGU206	90925	50.3	51.8	1.5	100	4A0			1.50	3.00	24.3					4.50		.67
FAGU206	90926	51.8	53.3	1.5	53	4A4			1.58	4.20	27.4					5.78		.73
FAGU206	90927	53.3	54.9	1.6	50	4A0			1.70	2.48	26.4					4.18		.59
FAGU206	90928	54.9	56.4	1.5	33	4E0			.63	1.30	11.0					1.93		.67
FAGU139	90929	42.7	44.2	1.5	100	4EL#			5.97	5.15	82.6					11.12		.46
FAGU206	90930	57.9	59.4	1.5	53	4A10			1.83	2.40	24.3					4.23		.57
FAGU206	90931	59.4	61.0	1.6	100	4CD5			2.20	5.50	30.2					7.70		.71
FAGU206	90932	61.0	62.5	1.5	33	4A0			1.35	2.88	21.3					4.23		.68
FAGU206	90933	62.5	64.0	1.5	100	4A34			5.42	7.70	67.5					13.12		.59
FAGU206	90934	64.0	65.5	1.5	60	4A34			6.65	10.55	80.6					17.20		.61
FAGU206	90935	65.5	67.1	1.6	87	4A34			7.61	11.66	102.9					19.27		.61
FAGU206	90936	67.1	68.5	1.4	36	4E4			9.89	16.00	138.2					25.89		.62
FAGU038	90937	11.1	12.2	1.1	100	4E4			2.35	5.52	33.3					7.87		.70
FAGU038	90938	12.2	13.7	1.5	100	4EA4			1.70	4.13	31.2					5.83		.71
FAGU038	90939	13.7	15.2	1.5	100	4E4			4.63	11.80	76.8					16.43		.72
FAGU038	90940	15.2	16.8	1.6	50	4E4			5.63	15.13	85.7					20.76		.73
FAGU038	90941	16.8	18.3	1.5	87	4G0			2.48	6.28	46.3					8.76		.72
FAGU038	90942	18.3	19.8	1.5	93	4G4			3.73	10.77	62.4					14.50		.74
FAGU038	90943	19.8	21.3	1.5	93	4G4			3.45	7.99	60.3					11.44		.70
FAGU038	90944	21.3	22.9	1.6	75	4G4			4.03	9.46	93.9					13.49		.70
FAGU038	90945	22.9	24.4	1.5	100	4ED4			6.20	12.50	104.9					18.70		.67
FAGU038	90946	24.4	25.9	1.5	100	4E4			5.42	10.15	75.8					15.57		.65
FAGU038	90947	25.9	27.4	1.5	100	4AD			4.25	6.02	71.7					10.27		.59
FAGU038	90948	27.4	29.0	1.6	100	4A13			.65	1.18	13.0					1.83		.64
FAGU076	90949	27.4	29.3	1.9	79	4E4			3.90	5.00	50.4					8.90		.56
FAGU076	90950	29.3	30.5	1.2	100	4E4			5.15	7.05	83.7					12.20		.58
FAGU076	90951	30.5	32.0	1.5	100	4E4			4.60	5.85	73.7					10.45		.56
FAGU076	90952	32.0	32.8	.8	100	4E4			6.92	10.21	86.7					17.13		.60
FAGU076	90953	32.8	34.3	1.5	93	4E4			4.30	5.10	57.6					9.40		.54
FAGU076	90954	34.3	36.4	2.1	95	4D4			12.04	12.77	183.4					24.81		.51
FAGU076	90955	36.4	38.5	2.1	95	4CEA			2.70	1.60	40.5					4.30		.37

DDH	SAMPLE	---DEPTHS---		INT M	REC %	ROCK UNIT	S.G.	CU %	PB %	ZN %	AG G/MT	AU G/MT	PO %	PY %	BAO %	PB+ZN %	PC+PY %	ZN RATIO		
		FROM	TO																	
FAGU076	90956	38.5	41.1	2.6	96	4A3			1.95	1.15	32.2								3.10	.37
FAGU076	90957	41.1	42.7	1.6	88	4A3			1.20	.25	20.2								1.45	.17
FAGU216	90969	62.8	64.0	1.2	100	3G0			1.68	2.80	30.2								4.48	.63
FAGU216	90970	64.0	65.5	1.5	100	4E4S			5.00	6.30	77.8								11.30	.56
FAGU216	90971	65.5	67.1	1.6	100	4EA			4.15	6.93	61.4								11.08	.63
FAGU216	90972	67.1	68.6	1.5	93	4A1			2.23	2.05	28.5								4.28	.48
FAGU216	90973	68.6	70.1	1.5	93	4A1			1.55	1.83	20.2								3.38	.54
FAGU216	90974	70.1	71.6	1.5	87	4AE4			5.60	10.17	70.6								15.77	.64
FAGU216	90975	71.6	73.6	2.0	100	4EAL			3.50	6.25	52.5								9.75	.64
FAGU216	90976	94.0	96.0	2.0	95	4A0			.23	.35	5.1								.58	.60
FAGU216	90977	96.0	97.5	1.5	100	4A0			.45	1.20	7.2								1.65	.73
FAGU216	90978	97.5	99.1	1.6	87	4A0			.08	.30	2.1								.38	.79
FAGA022	90979	356.7	357.5	.8	100	4L2			.47	.40	8.2								.87	.46
FAGU216	90980	100.6	102.1	1.5	93	4A0			.18	.30	3.1								.48	.63
FAGU216	90981	103.6	105.2	1.6	88	4A0			.08	.10	2.1								.18	.56
FAGU216	90982	105.2	106.7	1.5	93	4A0			.08	.43	2.1								.51	.84
FAGU216	90983	106.7	108.2	1.5	33	4AE			3.88	7.34	45.3								11.22	.65
FAGU216	90984	108.2	109.7	1.5	67	4A0			.30	.88	5.1								1.18	.75
FAGU216	90985	123.3	123.8	.5	100	4D34			9.40	9.30	90.9								18.70	.50
FAGU216	90986	126.5	128.0	1.5	100	4C8			1.88	1.93	18.2								3.81	.51
FAGU216	90987	128.0	129.5	1.5	100	4D8			2.75	2.35	30.2								5.10	.46
FAGA027	91000	160.3	160.9	.6	83	4A0			1.90	2.82	35.3								4.72	.60
FAGA027	91001	160.9	162.0	1.1	82	4A4			2.50	4.50	48.3								7.00	.64
FAGA027	91002	162.0	165.2	3.2	100	4A4			2.23	4.92	45.3								7.15	.69
FAGA027	91003	165.2	168.2	3.0	100	4A4			2.78	4.92	47.3								7.70	.64
FAGA027	91004	168.2	169.8	1.6	94	4A4			3.45	5.64	82.6								9.09	.62
FAGA027	91005	169.8	172.1	2.3	100	4A0			1.63	3.24	26.4								4.87	.67
FAGA027	91006	172.1	175.0	2.9	100	4C0			.93	.77	11.0								1.70	.45
FAGA027	91007	175.0	177.7	2.7	96	4C0			1.14	.89	16.1								2.03	.44
FAGA027	91008	177.7	180.7	3.0	100	4C0			2.00	2.10	26.4								4.10	.51
FAGA027	91009	180.7	183.3	2.6	92	4C0			3.08	.88	33.3								3.96	.22
FAGA027	91010	183.3	184.5	1.2	100	4D0			2.78	3.60	32.2								6.38	.56
FAGA027	91011	209.9	212.1	2.2	100	4D0			2.35	3.86	35.3								6.21	.62
FAGA027	91012	212.1	215.2	3.1	97	4C0			2.40	2.28	35.3								4.68	.49
FAGA027	91013	215.2	217.3	2.1	100	4D0			4.13	3.18	55.5								7.31	.44
FAGA027	91014	217.3	219.2	1.9	95	4A4			5.10	3.24	68.6								8.34	.39
FAGA027	91015	219.2	221.0	1.8	100	4A4			5.25	6.48	75.8								11.73	.55
FAGA027	91016	221.0	223.0	2.0	100	4A4			7.05	10.98	119.0								18.03	.61
FAGA027	91017	223.0	225.2	2.2	100	4A4			2.50	3.24	44.2								5.74	.56
FAGA027	91018	225.2	228.3	3.1	97	4C0			1.05	2.22	18.2								3.27	.68
FAGA027	91019	228.3	231.3	3.0	100	4C0			2.70	3.42	37.4								6.12	.56
FAGA027	91020	231.3	234.4	3.1	97	4C0			1.23	1.06	18.2								2.29	.46
FAGA027	91021	325.6	326.3	.7	100	4L0			.07	.16	1.0								.23	.70
FAGA069	91022	137.8	138.6	.8	100	4D4			6.31	8.39	91.9								14.70	.57
FAGA069	91023	160.8	162.2	1.4		4D0			2.43	4.62	35.3								7.05	.66
FAGA069	91024	207.3	209.2	1.9	95	4A4			2.30	5.58	44.2								7.88	.71
FAGA069	91025	220.2	221.4	1.2	75	4AD4			8.58	24.07	111.1								32.65	.74
FAGA069	91026	222.9	223.8	.9	100	4A4			5.74	14.43	105.9								20.17	.72

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAO	PB+ZN	PC+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGA069	91027	231.3	232.2	.9	100	4D4			9.25	19.60	145.0					28.85		.68
FAGA069	91028	312.4	314.2	1.8	100	4E4			5.95	9.13	83.6					15.08		.61
FAGA076	91029	139.5	140.5	1.0		4G48			6.70	10.65	62.4					17.35		.61
FAGA076	91030	140.5	142.1	1.6		4E4			4.65	7.20	66.5					11.85		.61
FAGA076	91031	142.1	143.6	1.5		4A4			3.75	5.28	52.4					9.03		.58
FAGA076	91032	284.5	285.4	.9	100	4A4			6.94	7.68	91.9					14.62		.53
FAGA076	91033	285.8	287.4	1.6		4D34			5.18	4.92	63.4					10.10		.49
FAGA076	91034	337.8	338.3	.5		4DE4			6.44	11.65	68.6					18.09		.64
FAGA076	91035	338.3	339.2	.9		4A10			.02	.06	1.0					.08		.74
FAGA076	91036	341.8	344.0	2.2		4DE			2.35	3.48	35.3					5.83		.60
FAGA076	91037	364.8	366.5	1.7		4E46			4.35	4.44	52.4					8.79		.51
FAGA076	91038	367.8	369.4	1.6		4G0			3.15	3.06	40.4					6.21		.49
FAGA076	91039	369.4	370.6	1.2		4G0			1.00	.31	12.0					1.31		.24
FAGA076	91040	370.6	372.2	1.6		4EG			4.73	3.60	48.3					8.33		.43
FAGA076	91041	372.2	373.4	1.2		4C3			1.60	.22	9.9					1.82		.12
FAGA076	91042	373.4	374.4	1.0		4G08			5.37	4.20	48.3					9.57		.44
FAGA076	91043	374.4	375.7	1.3		4C3			.59	.27	11.0					.86		.31
FAGA076	91044	375.7	377.3	1.6		4G08			5.03	3.66	50.4					8.69		.42
FAGA076	91045	377.3	378.7	1.4		4G08			4.05	3.42	39.4					7.47		.46
FAGA079	91046	89.3	90.8	1.5	100	4A4			3.30	5.46	45.3					8.76		.62
FAGA079	91047	90.8	92.5	1.7	100	4A4			2.93	5.40	37.4					8.33		.65
FAGA079	91048	92.5	96.0	3.5	40	4A4			4.13	2.82	44.2					6.95		.41
FAGA079	91049	96.0	97.4	1.4	93	4A0			1.58	1.94	25.4					3.52		.55
FAGA079	91050	97.4	99.4	2.0	100	4A0			1.35	2.46	23.3					3.81		.65
FAGA079	91051	99.4	100.9	1.5	100	4A4			2.50	4.26	35.3					6.76		.63
FAGA079	91052	100.9	102.4	1.5		4A0			1.48	3.00	21.3					4.48		.67
FAGA079	91053	102.4	104.5	2.1	86	4A4			1.90	4.14	29.1					6.04		.69
FAGA079	91054	106.8	109.7	2.9	90	4A0			.93	1.84	15.1					2.77		.66
FAGA079	91055	114.1	115.7	1.6	94	4A0			1.19	3.60	20.2					4.79		.75
FAGA079	91056	115.7	116.9	1.2	100	4A4			4.50	5.28	60.3					9.78		.54
FAGA079	91057	118.1	119.5	1.4	93	4D0			2.78	6.48	49.4					9.26		.70
FAGA079	91058	119.5	121.7	2.2	100	4DE			6.17	10.92	100.8					17.09		.64
FAGA079	91059	286.5	287.6	1.1	91	4AC			.85	1.74	12.0					2.59		.67
FAGA079	91060	287.6	289.4	1.8	100	4AD			2.23	4.26	39.4					6.49		.66
FAGA079	91061	289.8	291.8	2.0	95	4A4			2.28	3.60	36.3					5.88		.61
FAGA079	91062	291.8	292.4	.6	100	4A0			2.33	2.46	28.1					4.79		.51
FAGA079	91063	344.6	346.3	1.7	94	4E48			5.84	5.40	61.4					11.24		.48
FAGU135	91064	125.5	128.5	3.0	97	4L2			.53	1.00	11.0					1.53		.65
FAGU135	91065	128.5	131.5	3.0	100	4L0			.25	.13	5.1					.38		.34
FAGA069	91066	314.2	315.3	1.1	100	4E4			5.48	9.51	82.6					14.99		.63
FAGA052	91072	143.9	146.9	3.0	93	4A0			.25	.55	7.2					.80		.69
FAGA052	91073	146.9	149.0	2.1	100	4A0			.18	.44	7.2					.62		.71
FAGA023	91074	78.0	79.9	1.9		4E4	4.51	.12	13.00	20.80	164.0	1.51	1.88	22.70		33.80	24.58	.62
FAGA023	91075	79.9	83.1	3.2		4E4	4.99	.22	6.47	12.70	101.0	1.71	1.52	31.00		19.17	32.52	.66
FAGA023	91076	83.1	84.9	1.8		4A0	3.53	.11	1.83	2.25	33.0	1.17	.78	21.30		4.08	22.08	.55
FAGA023	91077	84.9	86.7	1.8		4A4	2.93	.06	2.67	4.50	37.0	.62	1.30	8.30		7.17	9.60	.63
FAGA071	91078	120.6	121.6	1.0	100	4E4			8.77	18.14	131.0					26.91		.67
FAGA071	91079	129.5	130.4	.9		4C0			1.48	2.40	22.3					3.88		.62
FAGA026	91081	46.6	49.7	3.1	35	4D5			1.55	3.84	25.4					5.39		.71

DDH	SAMPLE	---DEPTHS---		INT M	REC %	ROCK UNIT	S.G.	CU %	PB %	ZN %	AG G/MT	AU G/MT	PO %	PY %	BAO %	PB+ZN %	PC+PY %	ZN RATIO	
		FROM	TO																
FAGA026	91082	49.7	51.5	1.8	100	4D5			2.30	5.16	28.5							7.46	.69
FAGA026	91083	55.8	57.8	2.0	100	4D5			2.00	3.24	20.2							5.24	.62
FAGA026	91084	57.8	59.4	1.6	100	4E4			4.13	9.96	100.8							14.09	.71
FAGA026	91085	59.4	61.4	2.0	100	4E4			5.55	13.20	103.9							18.75	.70
FAGA026	91086	62.1	63.7	1.6	100	4E4			6.30	14.45	102.8							20.75	.70
FAGA026	91087	63.7	65.2	1.5		4E4			6.30	14.45	102.8							20.75	.70
FAGA026	91088	65.2	68.0	2.8	100	4E4			7.35	15.54	116.9							22.89	.68
FAGA026	91089	68.0	69.6	1.6	100	4E4			3.30	11.67	51.4							14.97	.78
FAGA026	91090	70.4	71.2	.8	100	4LE			3.15	6.24	51.4							9.39	.66
FAGA026	91091	71.2	72.5	1.3	100	4LE			.53	1.44	9.9							1.97	.73
FAGA026	91092	72.5	73.7	1.2	92	4LE			3.68	8.04	63.4							11.72	.69
FAGA026	91093	73.7	74.5	.8		4LE			6.60	16.30	105.9							22.90	.71
FAGA026	91094	96.5	98.3	1.8	100	4A13			1.58	1.06	22.3							2.64	.40
FAGA026	91095	98.3	100.6	2.3	96	4A134			3.08	3.72	35.3							6.80	.55
FAGA026	91096	100.6	103.3	2.7	96	4A13			.32	.74	6.2							1.06	.70
FAGA026	91097	103.3	105.0	1.7	88	4A13			1.38	1.35	17.1							2.73	.49
FAGA026	91098	105.0	106.2	1.2	100	4A134			7.05	8.04	97.7							15.09	.53
FAGA026	91099	106.2	109.0	2.8	93	4A13			1.35	3.00	20.2							4.35	.69
FAGA128	91100	237.8	239.8	2.0	95	4C#S			.93	.65	14.1							1.58	.41
FAGA128	91101	239.8	241.0	1.2	100	4E8			2.45	1.63	35.3							4.08	.40
FAGA128	91102	241.0	242.1	1.1	100	4G4			6.08	8.00	106.9							14.08	.57
FAGA128	91104	246.2	247.5	1.3	85	4D\$			2.23	3.28	28.5							5.51	.60
FAGA128	91105	317.6	318.2	.6	50	4E0			7.25	8.32	148.1							15.57	.53
FAGA128	91106	318.2	318.8	.6	83	4J24			15.59	23.00	302.4							38.59	.60
FAGA128	91107	347.8	348.8	1.0	90	4E0			4.13	4.86	53.5							8.99	.54
FAGA128	91108	352.2	353.6	1.4	86	4DA			1.58	1.50	22.3							3.08	.49
FAGA128	91109	353.6	355.1	1.5	93	4A10			1.13	1.08	21.3							2.21	.49
FAGA128	91110	355.1	356.6	1.5	87	4AD			1.31	1.50	19.2							2.81	.53
FAGA128	91111	356.6	360.0	3.4	68	4DAC			3.13	5.40	42.5							8.53	.63
FAGA128	91112	360.0	361.5	1.5	87	4CS			1.65	2.38	26.4							4.03	.59
FAGA128	91113	361.5	362.1	.6	100	4E4#			8.10	9.68	99.7							17.78	.54
FAGA128	91114	363.0	365.0	2.0	100	4G4			5.18	6.16	65.5							11.34	.54
FAGA128	91115	367.1	368.3	1.2	100	4E4@			6.74	8.65	100.8							15.39	.56
FAGA128	91116	368.3	370.0	1.7	94	4D\$			2.06	2.90	26.4							4.96	.58
FAGA128	91117	419.7	422.3	2.6	100	4C0			1.13	2.68	18.2							3.81	.70
FAGA128	91118	425.8	426.8	1.0	100	4L\$24			1.33	2.70	20.2							4.03	.67
FAGA128	91119	426.8	428.3	1.5	100	4EG			3.08	3.54	51.4							6.62	.53
FAGA128	91120	428.3	429.8	1.5	100	4EG			2.70	4.65	43.5							7.35	.63
FAGA128	91121	431.7	433.4	1.7	100	4E8			2.56	2.22	27.4							4.78	.46
FAGA128	91122	435.8	436.6	.8	100	4E4			3.00	3.42	34.3							6.42	.53
FAGA128	91123	436.6	437.6	1.0	100	4E4			4.13	2.46	40.4							6.59	.37
FAGA128	91124	437.6	438.6	1.0	100	4E4			3.98	3.20	35.3							7.18	.45
FAGA128	91125	438.6	439.6	1.0	100	4E4			5.89	6.32	50.4							12.21	.52
FAGA128	91126	444.7	445.9	1.2	100	4A0			3.30	2.52	36.3							5.82	.43
FAGA127	91127	93.5	96.5	3.0	93	4CA			1.70	2.88	26.4							4.58	.63
FAGA127	91128	96.5	99.5	3.0	93	4A4			1.78	4.50	40.4							6.28	.72
FAGA127	91129	99.5	102.5	3.0	90	4D5			2.08	5.34	43.5							7.42	.72
FAGA127	91130	102.5	105.5	3.0	20	4C5			1.68	2.88	25.4							4.56	.63
FAGA127	91131	105.5	108.5	3.0	100	4C5			1.20	3.30	26.4							4.50	.73
FAGA127	91132	108.5	111.5	3.0	100	4D5			1.38	3.66	25.4							5.04	.73

DDH	SAMPLE	---DEPTHS---	INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAO	PB+ZN	PC+PY	ZN
		FROM TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGA127	91133	111.5 114.5	3.0	100	4D5			1.68	4.20	38.4					5.88		.71
FAGA127	91134	114.5 117.5	3.0	100	4D5			1.78	4.02	35.3					5.80		.69
FAGA127	91135	117.5 120.5	3.0	97	4D5			1.58	3.96	29.1					5.54		.71
FAGA127	91136	120.5 123.7	3.2	94	4D5			2.15	4.86	38.4					7.01		.69
FAGA127	91137	162.5 165.8	3.3	100	4A0			1.28	3.54	23.3					4.82		.73
FAGA127	91138	235.9 237.2	1.3	100	4AE			5.61	9.78	85.7					15.39		.64
FAGA127	91139	237.2 240.7	3.5	97	4LA			.88	1.06	14.1					1.94		.55
FAGA127	91140	240.7 242.6	1.9	100	4A4			2.63	3.54	47.3					6.17		.57
FAGA127	91141	242.6 244.4	1.8	100	4D0			3.08	6.88	59.3					9.96		.69
FAGA127	91142	245.4 246.0	.6	100	4D0			2.30	6.84	48.3					9.14		.75
FAGA127	91143	327.5 329.5	2.0	100	4A4			4.73	6.29	76.8					11.02		.57
FAGA127	91144	329.5 332.4	2.9	86	4A4			3.68	4.56	56.6					8.24		.55
FAGA127	91145	334.2 334.6	.4	100	4E0			1.10	2.16	20.2					3.26		.66
FAGA127	91146	334.6 336.6	2.0	90	4E4			7.13	10.56	126.1					17.69		.60
FAGA127	91147	336.6 337.7	1.1	100	4EG			8.78	18.74	146.0					27.52		.68
FAGA127	91148	337.7 339.7	2.0	100	4EG			7.65	14.28	98.7					21.93		.65
FAGA127	91149	339.7 341.5	1.8	100	4EG			7.20	15.57	96.7					22.77		.68
FAGA127	91150	341.5 343.2	1.7	100	4AE			6.78	15.11	98.7					21.89		.69
FAGA127	91151	343.2 345.2	2.0	100	4AG			4.73	9.36	74.7					14.09		.66
FAGA127	91152	345.2 347.2	2.0	100	4AG			5.85	11.12	87.8					16.97		.66
FAGA127	91153	347.2 348.4	1.2	100	4G4			5.40	8.39	102.8					13.79		.61
FAGA127	91154	401.7 402.5	.8	100	3G916			4.80	5.76	57.6					10.56		.55
FAGA127	91155	402.5 403.4	.9	100	4G4			5.33	5.16	70.6					10.49		.49
FAGA127	91156	403.4 403.7	.3	67	3C4S			.25	.40	8.2					.65		.62
FAGA127	91157	403.7 404.7	1.0	100	4G0			4.43	4.14	75.8					8.57		.48
FAGA127	91158	404.7 406.0	1.3	100	4G4			6.38	9.34	106.9					15.72		.59
FAGA127	91159	406.0 408.2	2.2	100	4E86			1.78	.88	20.2					2.66		.33
FAGA127	91160	408.2 408.9	.7	100	4E86			.55	.53	12.0					1.08		.49
FAGA127	91161	408.9 409.6	.7	100	4E86			7.50	5.67	65.5					13.17		.43
FAGA127	91162	409.6 410.6	1.0	100	4E48			5.97	6.59	60.3					12.56		.52
FAGA127	91163	410.6 411.6	1.0	100	4C3			.35	.30	12.0					.65		.46
FAGA127	91164	411.6 412.6	1.0	100	4C3			.15	.14	8.9					.29		.48
FAGA127	91165	412.6 413.6	1.0	100	4C3			1.23	.72	23.3					1.95		.37
FAGA127	91166	413.6 414.6	1.0	100	4C3			.43	.50	14.1					.93		.54
FAGA127	91167	414.6 415.6	1.0	100	4C3			.48	1.25	16.1					1.73		.72
FAGA127	91168	415.6 416.6	1.0	100	4C3			1.18	.90	20.2					2.08		.43
FAGA127	91169	416.6 417.6	1.0	100	4C38			.75	.74	17.1					1.49		.50
FAGA127	91170	417.6 419.6	2.0	100	4C38			.53	.46	13.0					.99		.46
FAGA127	91171	419.6 421.1	1.5	100	4CEG			1.35	1.54	28.5					2.89		.53
FAGA125	91172	113.8 115.2	1.4	93	4AD			3.00	6.85	53.5					9.85		.70
FAGA125	91173	115.2 116.5	1.3	69	4A5D			.83	1.94	15.1					2.77		.70
FAGA125	91174	116.5 119.2	2.7	78	4A4			2.08	4.14	29.1					6.22		.67
FAGA125	91175	119.2 122.2	3.0	97	4A4			1.98	4.74	31.2					6.72		.71
FAGA125	91176	122.2 124.4	2.2	100	4D5			2.78	4.98	35.3					7.76		.64
FAGA125	91177	124.4 126.6	2.2	100	4D5			2.08	3.42	31.2					5.50		.62
FAGA125	91178	133.9 135.1	1.2	100	4A4			3.00	5.10	44.2					8.10		.63
FAGA125	91179	172.2 173.6	1.4	93	3G91			1.98	3.30	29.1					5.28		.63
FAGA125	91180	173.6 175.0	1.4	93	4A4			2.38	5.10	37.4					7.48		.68
FAGA125	91181	175.0 177.7	2.7	93	4A4			1.88	4.05	29.1					5.93		.68
FAGA125	91182	227.0 227.7	.7	100	4A4			3.53	4.30	54.5					7.83		.55

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAG	PB+ZN	PC+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGA125	91183	227.7	229.0	1.3	100	4AE			6.41	11.84	109.0					18.25		.65
FAGA125	91184	229.5	231.0	1.5	100	4A0			.75	1.18	9.9					1.93		.61
FAGA125	91185	317.6	318.6	1.0	100	4E14			5.42	6.50	90.8					11.92		.55
FAGA125	91186	321.9	322.8	.9	56	4D5			2.75	4.50	43.5					7.25		.62
FAGA125	91187	322.8	324.8	2.0	95	4D5			3.44	5.55	49.4					8.99		.62
FAGA125	91188	324.8	325.8	1.0	100	4C5			1.65	1.66	21.3					3.31		.50
FAGA125	91189	326.6	328.6	2.0	100	4A3\$4			2.85	3.98	38.4					6.83		.58
FAGA125	91190	328.6	331.1	2.5	100	4A3\$			1.63	2.10	28.5					3.73		.56
FAGA125	91191	336.5	337.6	1.1	100	3G6			2.50	2.70	25.4					5.20		.52
FAGA125	91192	340.6	342.6	2.0	95	4AD			1.38	2.20	16.1					3.58		.61
FAGA125	91193	344.0	345.6	1.6	100	4D45			3.23	4.05	39.4					7.28		.56
FAGA125	91194	355.1	355.7	.6	100	4A3			.83	1.08	16.1					1.91		.57
FAGA125	91195	355.7	356.7	1.0	100	4G4			5.18	8.75	85.7					13.93		.63
FAGA125	91196	356.7	357.4	.7	100	4G4			4.43	7.87	73.7					12.30		.64
FAGA125	91197	357.6	358.6	1.0	100	4G0			3.98	5.00	56.6					8.98		.56
FAGA125	91198	358.6	359.6	1.0	100	4G0			3.56	5.50	60.3					9.06		.61
FAGA125	91199	359.6	360.9	1.3	100	4GA			3.94	6.57	61.4					10.51		.63
FAGA125	91200	361.3	362.3	1.0	60	4E4			2.38	4.40	40.4					6.78		.65
FAGA125	91201	362.3	363.3	1.0	100	4E4			3.60	4.48	55.5					8.08		.55
FAGA125	91202	363.3	364.3	1.0	100	4E4			3.30	6.28	50.1					9.58		.66
FAGA125	91203	364.3	365.3	1.0	100	4E4			4.28	7.68	73.7					11.96		.64
FAGA125	91204	365.3	366.0	.7	100	4EG			5.18	7.56	94.6					12.74		.59
FAGA125	91205	381.3	383.3	2.0	100	4A0			.48	.52	13.0					1.00		.52
FAGA125	91206	383.3	385.3	2.0	100	4A0			.20	.18	12.0					.38		.47
FAGA125	91207	385.3	386.9	1.6	100	4A0			.65	.77	28.5					1.42		.54
FAGA125	91208	386.9	388.2	1.3	100	4A43			6.96	9.44	98.7					16.40		.58
FAGA125	91209	388.2	390.2	2.0	100	4A0			1.15	1.70	21.3					2.85		.60
FAGA125	91210	390.2	392.6	2.4	100	4A7			.38	.62	14.1					1.00		.62
FAGA125	91211	392.6	394.7	2.1	100	4ADH			3.83	2.88	46.3					6.71		.43
FAGA125	91212	403.4	405.9	2.5	100	4E4			2.85	3.12	42.5					5.97		.52
FAGA123	91213	113.2	115.0	1.8	100	4D0			2.38	3.48	37.4					5.86		.59
FAGA123	91214	115.0	116.0	1.0	100	4C0			1.83	2.00	24.3					3.83		.52
FAGA123	91215	116.0	118.0	2.0	100	4D0			1.93	3.54	26.4					5.47		.65
FAGA123	91216	118.0	120.0	2.0	100	4D0			1.90	3.48	29.1					5.38		.65
FAGA123	91217	120.0	122.0	2.0	100	4C0			1.75	3.18	26.4					4.93		.65
FAGA123	91218	122.0	124.0	2.0	100	4C0			1.99	3.00	28.5					4.99		.60
FAGA123	91219	127.6	128.9	1.3	100	4C0			1.84	2.76	29.1					4.60		.60
FAGA123	91220	128.9	130.0	1.1	100	4C0			1.48	2.46	24.3					3.94		.62
FAGA125	91221	132.6	134.4	1.8	28	4C0			1.23	1.66	28.5					2.89		.57
FAGA123	91222	134.4	135.9	1.5	60	4A4			2.50	4.02	36.3					6.52		.62
FAGA123	91223	135.9	136.8	.9	78	4A4			2.48	5.40	35.3					7.88		.69
FAGA123	91224	136.8	137.8	1.0	50	4C5			1.78	2.76	28.5					4.54		.61
FAGA123	91225	137.8	139.3	1.5	100	4AC			1.93	2.46	30.2					4.39		.56
FAGA123	91226	139.3	141.4	2.1	71	4A4			2.45	3.18	37.4					5.63		.56
FAGA123	91227	141.4	142.3	.9	89	4A4			2.59	3.90	41.5					6.49		.60
FAGA123	91228	142.3	144.5	2.2	27	4A4			2.70	4.02	43.5					6.72		.60
FAGA123	91229	144.5	145.4	.9	100	4D0			3.53	5.93	65.5					9.46		.63
FAGA123	91230	145.4	146.6	1.2	33	4A4			2.78	4.02	46.3					6.80		.59
FAGA123	91231	150.6	151.5	.9	100	4Q\$			1.23	1.18	21.3					2.41		.49
FAGA123	91232	156.5	158.5	2.0	90	4A4			2.50	4.38	40.4					6.88		.64

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAO	PB+ZN	PC+PY	ZN	
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO	
FAGA123	91233	158.5	160.0	1.5	93	4A4			2.78	4.20	44.2							6.98	.60
FAGA123	91234	160.0	160.7	.7	100	4A0			1.73	2.64	29.1							4.37	.60
FAGA123	91235	188.5	189.4	.9	89	4D0			1.53	3.48	19.2							5.01	.69
FAGA123	91236	189.4	191.1	1.7	100	4D0			2.18	5.40	31.2							7.58	.71
FAGA123	91237	191.6	193.5	1.9	16	4D0			2.93	5.64	33.3							8.57	.66
FAGA123	91238	193.5	194.5	1.0	60	4D4			23.00	7.20	50.4							30.20	.24
FAGA123	91239	194.5	195.7	1.2	92	4D4			3.75	8.00	63.4							11.75	.68
FAGA123	91240	195.7	196.3	.6	100	4D0			4.58	4.02	59.3							8.60	.47
FAGA123	91241	196.3	197.6	1.3	100	4D0			2.85	2.40	33.3							5.25	.46
FAGA123	91242	197.6	200.1	2.5	48	4A0			1.93	2.14	28.5							4.07	.53
FAGA123	91243	200.1	201.5	1.4	100	4A4			2.48	5.76	46.3							8.24	.70
FAGA123	91244	201.5	203.3	1.8	100	4A4			1.88	4.68	34.3							6.56	.71
FAGA123	91245	203.3	204.2	.9	56	4A4			1.70	4.08	26.4							5.78	.71
FAGA123	91246	204.2	205.5	1.3	100	4A4			2.18	1.47	25.4							3.65	.40
FAGA123	91247	209.4	211.2	1.8	100	4D0			3.60	3.60	38.4							7.20	.50
FAGA123	91248	229.6	230.7	1.1	100	4D0			2.85	6.29	48.3							9.14	.69
FAGA123	91249	230.8	231.9	1.1	100	4D0			2.63	4.50	36.3							7.13	.63
FAGA123	91250	231.9	233.5	1.6	100	5D4\$			1.23	1.40	18.2							2.63	.53
FAGA123	91251	233.5	234.2	.7	100	4D4			5.71	7.18	88.8							12.89	.56
FAGA123	91252	234.6	236.1	1.5	100	4A0			1.18	1.70	19.2							2.88	.59
FAGA123	91253	236.1	237.6	1.5	100	3G0			.58	.76	7.2							1.34	.57
FAGA123	91254	239.1	239.9	.8	100	4C0			2.38	2.14	33.3							4.52	.47
FAGA123	91255	244.0	246.0	2.0	100	4A0			4.65	6.90	68.6							11.55	.60
FAGA123	91256	246.0	248.0	2.0	100	4A4			4.73	8.11	77.8							12.84	.63
FAGA123	91257	248.0	250.0	2.0	100	4A4			4.20	8.07	64.5							12.27	.66
FAGA123	91258	250.0	251.8	1.8	100	5B26			.75	1.54	12.0							2.29	.67
FAGA123	91259	251.8	253.0	1.2	100	4A44			7.73	16.75	143.3							24.48	.68
FAGA123	91260	253.0	254.0	1.0	100	4A4			2.70	4.02	46.3							6.72	.60
FAGA123	91261	273.1	274.6	1.5	100	4E4			5.21	11.86	84.7							17.07	.69
FAGA123	91262	274.6	275.7	1.1	100	4E4			6.93	14.44	123.1							21.37	.68
FAGA123	91263	278.0	279.3	1.3	100	4A4			2.43	5.64	38.4							8.07	.70
FAGA123	91264	279.3	281.0	1.7	100	4D4			5.11	6.05	76.8							11.16	.54
FAGA123	91265	281.0	282.5	1.5	100	4A0			3.75	5.86	58.6							9.61	.61
FAGA123	91266	282.5	284.0	1.5	100	4A4			4.35	5.64	73.7							9.99	.56
FAGA123	91267	284.0	285.6	1.6	94	4A4			4.95	7.58	85.7							12.53	.60
FAGA123	91268	285.6	286.7	1.1	100	4A4			3.68	7.69	68.6							11.37	.68
FAGA123	91269	299.1	300.4	1.3	100	4A4			2.63	3.42	44.2							6.05	.57
FAGA123	91270	300.4	302.0	1.6	81	4C5			1.15	2.10	18.2							3.25	.65
FAGA123	91271	302.0	304.0	2.0	95	4A0			1.88	2.76	30.2							4.64	.59
FAGA123	91272	304.0	306.0	2.0	100	4A4			3.15	4.92	50.4							8.07	.61
FAGA123	91273	306.0	307.2	1.2	100	4A4			3.98	6.23	60.3							10.21	.61
FAGA123	91274	316.3	317.8	1.5	100	3G46			.40	1.36	5.1							1.76	.77
FAGA123	91275	317.8	319.4	1.6	100	3G46			.38	.95	4.1							1.33	.71
FAGA123	91276	320.6	322.6	2.0	100	4L74			.50	.92	8.9							1.42	.65
FAGA123	91277	322.6	324.5	1.9	100	4L74			.23	.52	5.1							.75	.69
FAGA123	91278	374.0	375.2	1.2	100	3C4\$			1.68	1.92	25.4							3.60	.53
FAGA123	91279	375.2	376.4	1.2	100	4G4			7.65	11.53	126.1							19.18	.60
FAGA123	91280	376.4	377.4	1.0	100	4G4			4.95	5.76	68.6							10.71	.54
FAGA123	91281	378.9	380.2	1.3	92	4E\$4			3.83	2.10	50.4							5.93	.35
FAGA123	91282	383.4	384.1	.7	100	4E\$4			7.41	3.18	106.9							10.59	.30

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAO	PB+ZN	PC+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGA123	91283	384.8	385.6	.8	100	4E\$4			2.48	3.48	42.5					5.96		.58
FAGA123	91284	385.6	386.8	1.2	100	3C2			.70	1.28	15.1					1.98		.65
FAGA123	91285	390.4	391.7	1.3	100	4E0			1.95	3.06	33.3					5.01		.61
FAGA123	91286	391.7	392.9	1.2	100	4E4			3.15	3.12	45.3					6.27		.50
FAGA123	91287	392.9	394.6	1.7	100	4A43			4.92	8.35	76.8					13.27		.63
FAGA123	91288	399.0	400.2	1.2	100	4A30			.65	1.00	29.1					1.65		.61
FAGA123	91289	400.2	402.0	1.8	100	4C3			.68	1.44	20.2					2.12		.68
FAGA123	91290	402.8	404.0	1.2	100	4E6			3.98	4.86	52.4					8.84		.55
FAGA123	91291	404.0	405.5	1.5	100	4E8			1.88	1.92	30.2					3.80		.51
FAGA123	91292	405.5	406.6	1.1	100	4G4			6.98	8.87	112.1					15.85		.56
FAGA123	91293	406.6	408.1	1.5	100	4G4			6.38	9.36	103.9					15.74		.59
FAGA123	91294	421.8	422.9	1.1	100	3G16			.45	.46	11.0					.91		.51
FAGA123	91295	422.9	423.6	.7	100	4E81			.65	.46	18.2					1.11		.41
FAGA123	91296	423.6	424.7	1.1	100	4A0			.55	.64	11.0					1.19		.54
FAGA123	91297	438.8	440.4	1.6	100	4HA			1.55	.64	11.0					2.19		.29
FAGA059	91298	258.7	260.5	1.8	100	4EA			5.93	11.11	90.8					17.04		.65
FAGA059	91299	260.5	262.1	1.6	100	4A4			2.10	4.20	37.4					6.30		.67
FAGA059	91300	262.1	265.2	3.1	100	4A0			1.28	2.52	22.3					3.80		.66
FAGA059	91301	265.2	268.2	3.0	100	4AC			1.88	3.96	30.2					5.84		.68
FAGA059	91302	268.2	268.9	.7	100	4C5			1.38	1.38	19.2					2.76		.50
FAGA059	91303	269.8	271.7	1.9	100	4AC			1.65	3.18	25.4					4.83		.66
FAGA059	91304	271.7	273.5	1.8	100	4D5			2.40	4.02	34.3					6.42		.63
FAGA059	91305	273.5	274.3	.8	100	4C5			1.23	2.34	17.1					3.57		.66
FAGA059	91306	280.1	283.3	3.2	100	5A19			.15	.28	3.1					.43		.63
FAGA059	91307	283.3	284.0	.7	100	5A19			.85	1.36	13.0					2.21		.62
FAGA059	91308	284.5	285.3	.8	100	4A0			.73	1.24	12.0					1.97		.63
FAGA059	91309	285.6	287.2	1.6	94	4A0			1.03	1.98	14.1					3.01		.66
FAGA059	91310	287.2	288.6	1.4	100	4A0			.66	1.60	8.2					2.26		.71
FAGA059	91311	288.6	290.3	1.7	100	4C5			.30	.44	4.1					.74		.60
FAGA059	91312	308.5	310.4	1.9	100	4A0			.49	.94	7.2					1.43		.66
FAGA059	91313	310.4	312.8	2.4	92	4AC			.44	1.00	7.2					1.44		.69
FAGA059	91314	312.8	315.0	2.2	100	4C5			1.38	2.34	21.3					3.72		.63
FAGA059	91315	315.0	316.2	1.2	100	4C0			.65	.95	9.9					1.60		.59
FAGA059	91316	316.2	318.8	2.6	100	4C0			.65	1.24	9.9					1.89		.66
FAGA059	91317	318.8	321.9	3.1	90	4C0			.65	1.14	9.9					1.79		.64
FAGA059	91318	321.9	323.4	1.5	80	4A0			.63	.56	6.2					1.19		.47
FAGA059	91319	323.4	324.7	1.3	100	3C4\$			.07	.09	1.0					.16		.56
FAGA059	91320	324.7	327.1	2.4	88	4A4			3.53	6.12	46.3					9.65		.63
FAGA059	91321	327.1	327.8	.7	100	4A30			1.28	1.40	17.1					2.68		.52
FAGA059	91322	327.8	329.7	1.9	100	4A30			.90	.45	20.2					1.35		.33
FAGA059	91323	329.7	331.6	1.9	100	4DG			6.15	10.38	100.8					16.53		.63
FAGA059	91324	331.6	333.4	1.8	100	4G4			4.95	8.52	90.8					13.47		.63
FAGA059	91325	333.4	335.4	2.0	100	4E4			8.43	14.39	104.9					22.82		.63
FAGA059	91326	335.4	336.9	1.5	80	4E#4			5.70	11.67	121.0					17.37		.67
FAGA059	91327	336.9	337.5	.6	100	3C4\$			1.45	2.40	23.3					3.85		.62
FAGA059	91328	337.5	337.8	.3	100	3C4\$			.14	.72	6.2					.86		.84
FAGA059	91329	337.8	340.0	2.2	41	5A6\$			.19	.38	2.1					.57		.67
FAGA059	91330	340.0	340.3	.3	100	4E4\$			9.65	16.21	201.6					25.86		.63
FAGA059	91331	340.3	341.0	.7	71	3G4			.05	.18	6.2					.23		.78
FAGA059	91332	341.0	341.4	.4	100	4E46			14.61	19.44	196.8					34.05		.57

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAO	PB+ZN	PC+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGA059	91333	341.4	343.1	1.7	100	5A6\$			.07	.12	2.1					.19		.63
FAGA059	91334	343.1	344.5	1.4	86	4E46\$			11.00	17.19	176.5					28.19		.61
FAGA059	91335	380.5	381.7	1.2	100	4A0			2.33	2.52	53.1					4.85		.52
FAGA059	91336	381.7	382.9	1.2	92	4G0			3.00	4.62	68.6					7.62		.61
FAGA059	91337	384.1	384.4	.3	100	4G4			4.50	8.16	43.5					12.66		.64
FAGA059	91338	384.7	387.2	2.5	100	4G4			5.10	8.28	73.7					13.38		.62
FAGA059	91339	387.2	387.6	.4	100	4L4\$			.68	.40	8.2					1.08		.37
FAGA059	91340	387.6	389.8	2.2	100	4G4			6.30	9.41	100.8					15.71		.60
FAGA059	91341	389.8	390.9	1.1	100	4G4			5.70	8.52	100.8					14.22		.60
FAGA059	91342	390.9	392.4	1.5	93	4G4			5.70	8.64	80.6					14.34		.60
FAGA059	91343	392.4	393.6	1.2	100	4L12			2.10	1.84	44.2					3.94		.47
FAGA061	91344	240.5	242.2	1.7	94	5A6\$			.39	.72	6.2					1.11		.65
FAGA061	91345	242.2	243.2	1.0	100	5A6\$			1.40	2.46	17.1					3.86		.64
FAGA061	91346	243.2	244.1	.9	89	4E14			1.93	4.02	40.4					5.95		.68
FAGA061	91347	244.1	245.3	1.2	92	5C4\$			1.05	1.66	11.0					2.71		.61
FAGA061	91348	256.0	257.6	1.6	88	4Q43			1.88	2.64	35.3					4.52		.58
FAGA061	91349	264.1	265.8	1.7	100	4C0			1.55	1.88	22.3					3.43		.55
FAGAC61	91350	265.8	268.6	2.8	100	4A0			1.85	3.00	32.6					4.85		.62
FAGA061	91351	268.6	271.6	3.0	100	4AC			1.50	1.72	22.3					3.22		.53
FAGA061	91352	271.6	273.5	1.9	100	4A0			1.28	1.76	19.2					3.04		.58
FAGA061	91353	273.5	276.4	2.9	100	4A0			1.10	1.54	15.1					2.64		.58
FAGA020	91354	325.0	328.0	3.0	100	4CA0			1.13	1.04	16.1					2.17		.48
FAGA020	91355	332.5	333.5	1.0	80	4GE4			4.43	6.21	77.8					10.64		.58
FAGA020	91356	337.7	338.5	.8	100	4GA			2.08	2.28	53.5					4.36		.52
FAGA020	91357	338.5	340.2	1.7	100	4GA			1.63	2.88	32.2					4.51		.64
FAGA020	91358	343.2	344.8	1.6	100	4EG			3.38	5.55	67.5					8.93		.62
FAGA020	91359	351.0	352.0	1.0	100	4E4			2.78	2.46	45.3					5.24		.47
FAGA020	91360	352.0	353.0	1.0	100	4E4			3.00	2.94	35.3					5.94		.49
FAGA020	91361	355.0	356.7	1.7	100	4G4			5.03	6.66	78.8					11.69		.57
FAGA020	91362	360.6	361.6	1.0	100	4CE4			3.15	6.33	47.3					9.48		.67
FAGA020	91363	362.7	363.9	1.2	100	4E4			4.43	7.94	63.4					12.37		.64
FAGA020	91364	363.9	364.7	.8	100	4E4			2.20	3.18	40.4					5.38		.59
FAGA020	91365	364.7	366.0	1.3	100	4C0			1.03	1.94	25.4					2.97		.65
FAGA020	91366	366.0	367.0	1.0	100	4C3			1.40	2.22	30.2					3.62		.61
FAGAC20	91367	367.0	368.0	1.0	100	4C3			1.70	2.94	34.3					4.64		.63
FAGAC20	91368	368.0	369.0	1.0	100	4C0			1.50	1.60	30.2					3.10		.52
FAGA020	91369	370.0	371.0	1.0	100	4DC			3.75	4.32	64.5					8.07		.54
FAGA020	91370	371.0	372.2	1.2	100	4H4			3.90	4.02	60.3					7.92		.51
FAGA020	91371	372.2	372.6	.4	100	4H0			1.90	1.84	46.3					3.74		.49
FAGAC20	91372	372.6	374.7	2.1	100	4EC			1.75	2.70	32.2					4.45		.61
FAGA020	91373	257.0	258.5	1.5	100	5B9		.05	.98	1.74	24.7		.34			2.72		.64
FAGU187	91374	16.8	18.3	1.5	93	4A0			.10	.70	4.1					.80		.88
FAGU187	91375	18.3	19.8	1.5	87	4A13			.43	.78	15.1					1.21		.64
FAGU187	91376	19.8	21.3	1.5	87	4A13			1.48	2.85	20.2					4.33		.66
FAGU187	91377	21.3	22.9	1.6	100	4A13			3.05	3.55	40.5					6.60		.54
FAGU187	91378	22.9	24.4	1.5	100	4A13			1.23	1.33	17.1					2.56		.52
FAGU187	91379	24.4	25.9	1.5	93	4A13			1.10	1.48	15.1					2.58		.57
FAGU187	91380	25.9	27.4	1.5	93	4A13			1.93	1.85	20.2					3.78		.49
FAGU187	91381	27.4	29.0	1.6	100	4A13			.98	2.05	31.2					3.03		.68
FAGU187	91382	29.0	30.5	1.5	100	4A13			.60	1.33	8.2					1.93		.69



NDH	SAMPLE	---DEPTHS---		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAO	PB+ZN	PC+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGU209	91433	45.7	47.2	1.5	67	4E4*			6.49	10.25	108.0					16.74		.61
FAGU209	91434	47.2	48.7	1.5	60	4E4*			4.55	6.41	69.6					10.96		.58
FAGU209	91435	48.7	50.2	1.5	53	4E4*			3.48	5.30	48.3					8.78		.60
FAGU209	91436	50.2	51.9	1.7	59	4A0			1.05	1.90	16.1					2.95		.64
FAGU210	91437	51.9	53.0	3.0	23	4D54			6.42	4.55	71.7					10.97		.41
FAGU210	91438	53.0	54.5	1.5	87	5D4*			.85	2.70	14.1					3.55		.76
FAGU210	91439	54.5	56.0	1.5	80	4D4			3.73	8.11	56.6					11.84		.68
FAGU210	91440	56.0	57.5	1.5	100	4D4			3.70	7.90	53.5					11.60		.68
FAGU210	91441	57.5	59.0	1.5	53	5D4*			2.30	4.80	33.3					7.10		.68
FAGU210	91442	59.0	60.5	1.5	93	4D45			3.78	6.90	58.6					10.68		.65
FAGU210	91443	60.5	62.0	1.5	73	4D5			3.20	6.55	46.3					9.75		.67
FAGU210	91444	62.0	63.5	1.5	73	5D4*			2.90	5.30	48.3					8.20		.65
FAGU210	91445	63.5	65.0	1.5	100	4D45			3.82	9.05	68.6					12.87		.70
FAGU210	91446	65.0	66.5	1.5	87	4D45			4.13	9.01	78.9					13.14		.69
FAGU210	91447	66.5	68.0	1.5	73	4C5			1.38	3.13	23.3					4.51		.69
FAGU210	91448	68.0	69.5	1.5	60	4D5			2.88	6.92	50.4					9.80		.71
FAGU210	91449	69.5	71.0	1.5	100	4D45			7.83	13.57	125.1					21.40		.63
FAGU210	91450	71.0	72.5	1.5	100	4D45			5.00	9.74	80.6					14.74		.66
FAGU210	91451	72.5	74.0	1.5	100	4A4			2.63	5.63	42.5					8.26		.68
FAGU210	91452	74.0	75.5	1.5	100	5D4*			.53	.25	8.2					.78		.32
FAGU210	91453	75.5	77.1	1.6	94	4A3			1.75	1.48	27.4					3.23		.46
FAGU210	91454	77.1	78.0	2.2	100	4E4\$			7.68	16.70	140.2					24.38		.69
FAGU210	91455	78.0	79.4	2.0	90	4A4			6.19	7.87	79.5					14.06		.56
FAGU210	91456	79.4	80.9	1.5	100	4LDE			6.22	9.59	88.8					15.81		.61
FAGU210	91457	80.9	82.4	1.5	100	4E4			4.87	7.52	71.7					12.39		.61
FAGU210	91458	82.4	83.9	1.5	100	4E4			5.00	7.70	69.6					12.70		.61
FAGU210	91459	83.9	85.4	1.5	100	4AE			5.63	10.60	81.6					16.23		.65
FAGU210	91460	85.4	86.9	1.5	73	4AC			1.13	1.45	15.1					2.58		.56
FAGU210	91461	86.9	88.9	3.0	57	4A0			.58	.73	13.0					1.31		.56
FAGU210	91462	88.9	90.4	1.5	100	4A0			.18	.65	14.1					.83		.78
FAGU210	91463	90.4	91.9	1.5	73	4A0			.15	.28	8.2					.43		.65
FAGU210	91464	91.9	93.9	3.0	70	4A0			.33	1.08	8.2					1.41		.77
FAGU210	91465	93.9	95.4	1.5	100	4A0			.73	1.35	13.0					2.08		.65
FAGU210	91466	95.4	96.9	1.5	87	4A0			.05	.45	3.1					.50		.90
FAGU210	91467	96.9	98.9	3.0	73	4A0			.05	.33	5.1					.38		.87
FAGU210	91468	98.9	100.9	3.0	97	4A0			.07	1.05	4.1					1.12		.94
FAGU210	91469	100.9	102.9	2.0	100	4EC			1.00	1.63	23.3					2.63		.62
FAGU210	91470	102.9	104.4	1.2	100	4D45			6.99	12.52	98.7					19.51		.64
FAGU211	91471	104.4	106.6	3.4	32	4AC			1.58	2.55	22.3					4.13		.62
FAGU211	91472	106.6	108.6	3.0	53	4C5			1.13	.88	14.1					2.01		.44
FAGU211	91473	108.6	110.6	1.5	87	4C5			1.68	1.53	20.2					3.21		.48
FAGU211	91474	110.6	112.6	1.5	73	4C5			1.03	1.83	14.1					2.86		.64
FAGU211	91475	112.6	114.6	3.0	30	4C5			.90	.93	9.9					1.83		.51
FAGU211	91476	114.6	116.6	3.0	40	4AC			1.53	.75	19.2					2.28		.33
FAGU211	91477	116.6	118.6	3.0	37	4A4			4.50	6.55	59.3					11.05		.59
FAGU211	91478	118.6	120.6	1.5	67	4A4			1.90	3.35	26.4					5.25		.64
FAGU211	91479	120.6	122.6	1.5	60	4A4			3.58	7.48	45.3					11.06		.68
FAGU211	91480	122.6	124.1	1.5	53	4A4			3.93	7.54	51.4					11.47		.66
FAGU211	91481	124.1	125.9	1.8	44	4AC			1.08	2.95	18.2					4.03		.73
FAGU211	91482	125.9	127.4	1.5	100	4E4			8.99	15.07	159.4					24.06		.63

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAO	PB+ZN	PC+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGU211	91483	27.4	28.1	.7	100	4E4			6.43	9.22	110.1					15.65		.59
FAGU211	91484	35.4	36.9	1.5	100	4AEG			2.63	4.85	59.3					7.48		.65
FAGU211	91485	36.9	38.4	1.5	100	4G4			4.48	8.19	69.6					12.67		.65
FAGU211	91486	38.4	39.5	1.1	100	4G4			3.40	7.16	72.7					10.56		.68
FAGU211	91487	39.5	41.0	1.5	100	4G4			4.50	7.24	75.8					11.74		.62
FAGU211	91488	41.0	42.5	1.5	100	4G4			5.00	7.87	74.7					12.87		.61
FAGU211	91489	42.5	44.3	1.8	94	4E4			2.85	3.20	60.3					6.05		.53
FAGU211	91490	71.6	73.1	1.5	100	4D4			4.33	6.44	64.5					10.77		.60
FAGU211	91491	73.1	74.6	1.5	100	4C3			1.80	2.15	33.3					3.95		.54
FAGU211	91492	74.6	76.1	1.5	93	4D53			2.68	4.75	42.5					7.43		.64
FAGU211	91493	76.1	77.6	1.5	100	4D53			2.73	2.60	46.3					5.33		.49
FAGU211	91494	77.6	79.1	1.5	100	4C3			.25	.53	11.0					.78		.68
FAGU211	91495	79.1	80.6	1.5	93	4C3			.40	.80	15.1					1.20		.67
FAGU211	91496	80.6	82.1	1.5	93	4C3			.05	.55	9.9					.60		.92
FAGU211	91497	82.1	83.6	1.5	100	4C3			.30	.65	13.0					.95		.68
FAGU211	91498	83.6	85.1	1.5	100	4C3			.25	.65	12.0					.90		.72
FAGU211	91499	85.1	86.6	1.5	100	4C3			.80	2.00	24.3					2.80		.71
FAGU211	91500	86.6	88.1	1.5	100	4D4			5.56	6.56	73.7					12.12		.54
FAGU212	91501	10.7	11.2	.5	100	4A0			1.30	2.73	15.1					4.03		.68
FAGU212	91502	11.2	12.2	1.0	100	4C5			1.48	1.93	19.2					3.41		.57
FAGU212	91503	12.2	13.7	1.5	100	4C0			2.15	1.60	24.3					3.75		.43
FAGU212	91504	13.7	15.2	1.5	87	4D0			3.40	3.00	40.5					6.40		.47
FAGU212	91505	15.2	16.8	1.6	94	4D0			2.60	3.55	32.2					6.15		.58
FAGU212	91506	16.8	18.3	1.5	80	4C0			2.23	2.75	28.5					4.98		.55
FAGU212	91507	18.3	19.8	1.5	100	4C0			1.68	2.65	20.2					4.33		.61
FAGU212	91508	19.8	21.3	1.5	100	4C0			.40	.63	5.1					1.03		.61
FAGU212	91509	21.3	22.9	1.6	62	4C0			1.48	2.00	20.2					3.48		.57
FAGU212	91510	30.0	32.0	2.0	100	4C0			.50	.78	8.2					1.28		.61
FAGU212	91511	32.0	33.5	1.5	100	4A0			.33	1.18	6.2					1.51		.78
FAGU212	91512	33.5	36.0	2.5	100	4A4			1.88	3.73	29.1					5.61		.66
FAGU212	91513	36.0	38.1	2.1	95	4E4			8.05	15.78	119.0					23.83		.66
FAGU212	91514	41.9	42.7	.8	100	4E46			7.39	9.26	114.5					16.65		.56
FAGU212	91515	42.7	44.2	1.5	100	4E46			5.75	6.01	119.0					11.76		.51
FAGU212	91516	44.2	45.7	1.5	100	4E46			4.53	7.53	87.8					12.06		.62
FAGU212	91517	45.7	47.2	1.5	100	4G4			4.68	8.60	68.6					13.28		.65
FAGU212	91518	47.2	48.8	1.6	100	4G4			5.30	8.88	81.6					14.18		.63
FAGU212	91519	48.8	50.3	1.5	100	4G0			2.56	5.89	41.5					8.45		.70
FAGU212	91520	50.3	51.8	1.5	100	4G4			3.70	6.65	59.3					10.35		.64
FAGU212	91521	51.8	53.3	1.5	67	4E4			4.95	7.30	68.6					12.25		.60
FAGU212	91522	54.9	56.4	1.5	53	4E\$4			3.15	6.06	51.4					9.21		.66
FAGU212	91523	56.4	59.1	2.7	37	4E46			4.20	8.04	80.6					12.24		.66
FAGU212	91524	59.1	61.0	1.9	100	4ED4			6.29	12.70	93.9					18.99		.67
FAGU212	91525	61.0	62.5	1.5	100	4E4\$			4.00	3.60	57.6					7.60		.47
FAGU212	91526	62.5	64.0	1.5	100	4EGD			9.15	15.98	118.6					25.13		.64
FAGU212	91527	64.0	65.5	1.5	100	4E4\$			3.85	4.15	46.3					8.00		.52
FAGU212	91528	65.5	67.1	1.6	94	4E0\$			2.80	1.70	39.8					4.50		.38
FAGU212	91529	67.1	68.6	1.5	93	4E4*			7.58	14.12	127.9					21.70		.65
FAGU212	91530	68.6	70.2	1.6	94	4E4*			3.38	3.80	47.3					7.18		.53
FAGU213	91531	51.2	52.7	1.5	73	4E4			3.83	6.86	63.4					10.69		.64
FAGU213	91532	52.7	54.2	1.5	80	4E4#			2.58	4.45	41.5					7.03		.63

DDH	SAMPLE	---DEPTHS---	INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAG	PB+ZN	PC+PY	ZN
		FROM TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGU213	91533	54.2	55.7	1.5	93	4E4#		4.23	7.70	58.6					11.93		.65
FAGU213	91534	55.7	57.2	1.5	73	4G0		3.23	6.12	54.5					9.35		.65
FAGU213	91535	57.2	58.7	1.5	80	4EG4		4.08	7.05	71.7					11.13		.63
FAGU213	91536	58.7	60.2	1.5	60	4E4#		5.97	9.17	94.6					15.14		.61
FAGU213	91537	60.2	61.7	1.5	60	4EG4		3.85	6.70	50.4					10.55		.64
FAGU213	91538	61.7	63.2	1.5	60	4EG4		5.79	8.39	78.9					14.18		.59
FAGU213	91539	63.2	64.7	1.5	73	4EG#		1.50	1.63	31.2					3.13		.52
FAGU213	91540	64.7	66.2	1.5	53	4E0#		1.28	1.20	30.2					2.48		.48
FAGU213	91541	66.2	67.7	1.5	67	4E4#		2.75	4.60	52.5					7.35		.63
FAGU213	91542	67.7	69.2	1.5	73	4E0#		1.53	2.45	28.5					3.98		.62
FAGU213	91543	69.2	70.7	1.5	67	4A34		2.93	5.00	46.3					7.93		.63
FAGU213	91544	70.7	72.2	1.5	67	4A30		.85	1.53	17.1					2.38		.64
FAGU213	91545	72.2	73.7	1.5	47	4A34		1.83	4.40	24.3					6.23		.71
FAGU213	91546	73.7	75.2	1.5	60	4A0		.85	1.83	13.0					2.68		.68
FAGU213	91547	75.2	76.7	1.5	60	4A0		.83	1.03	16.1					1.86		.55
FAGU213	91548	76.7	78.2	1.5	67	4A0		1.10	1.88	27.4					2.98		.63
FAGU213	91549	78.2	79.7	1.5	67	4AE		9.14	15.62	120.0					24.76		.63
FAGU213	91550	79.7	81.2	1.5	67	4AE		4.58	8.31	68.6					12.89		.64
FAGU213	91551	81.2	82.7	1.5	87	4A0		.88	1.38	28.1					2.26		.61
FAGU213	91552	82.7	84.2	1.5	87	4A0		.18	.80	12.0					.98		.82
FAGU213	91553	84.2	85.7	1.5	87	4DE4		6.37	13.89	88.8					20.26		.69
FAGU213	91554	85.7	87.2	1.5	87	4A43		5.70	11.23	70.6					16.93		.66
FAGU213	91555	87.2	88.7	1.5	100	4A43		2.43	4.45	33.3					6.88		.65
FAGU213	91556	88.7	90.2	1.5	100	4A31		.68	1.30	20.2					1.98		.66
FAGU213	91557	90.2	91.7	1.5	93	4A31		.45	1.28	17.1					1.73		.74
FAGU213	91558	91.7	93.2	1.5	87	4A31		.30	1.00	13.0					1.30		.77
FAGU213	91559	93.2	94.7	1.5	87	4A31		.18	.98	12.0					1.16		.85
FAGU213	91560	94.7	96.2	1.5	100	4A31		.20	1.28	6.2					1.48		.86
FAGU213	91561	96.2	97.7	1.5	100	4A31		.88	1.68	12.0					2.56		.66
FAGU213	91562	97.7	99.2	1.5	93	4A31		.43	2.53	11.0					2.96		.85
FAGU213	91563	99.2	100.7	1.5	67	4A31		.05	.85	9.9					.90		.94
FAGU213	91564	100.7	102.2	1.5	67	4A31		.05	1.03	9.9					1.08		.95
FAGU213	91565	102.2	103.7	1.5	100	4C3		.02	.43	8.9					.45		.96
FAGU213	91566	103.7	105.2	1.5	100	4E0		.03	1.00	7.9					1.03		.97
FAGU213	91567	105.2	106.7	1.5	100	4A0		.02	.75	5.1					.77		.97
FAGU213	91568	106.7	108.9	2.2	100	4E10		1.28	1.63	29.1					2.91		.56
FAGU213	91569	113.9	114.7	.8	100	4G4		6.75	12.22	88.8					18.97		.64
FAGU208	91570	33.0	34.0	1.0	90	3G0		1.85	4.88	27.4					6.73		.73
FAGU209	91571	57.9	59.4	1.5		4A0		1.98	2.83	22.3					4.81		.59
FAGU100	91572	24.4	25.9	1.5	100	4A4		2.78	4.55	36.3					7.33		.62
FAGA067	91573	284.1	285.0	.9		4E64		4.13	5.88	60.0					10.01		.59
FAGA067	91574	182.8	184.9	2.1		4A14		2.33	3.90	34.0					6.23		.63
FAGA067	91575	186.5	189.0	2.5		4A14		2.18	4.26	33.0					6.44		.66
FAGA067	91576	194.2	196.0	1.8		4A14		2.15	4.62	35.0					6.77		.68
FAGA078	91577	51.7	53.2	1.5	-33	4D4		5.40	9.22	90.8					14.62		.63
FAGA078	91578	54.6	55.3	.7	-71	4D4		6.38	13.30	90.8					19.68		.68
FAGA078	91579	56.8	58.0	1.2	-42	4D4		3.90	8.04	59.7					11.94		.67
FAGA078	91580	74.6	76.1	1.5	-33	4D47		5.03	4.80	65.5					9.83		.49
FAGA078	91581	78.6	80.8	2.2	-23	4D45		8.72	14.83	126.1					23.55		.63
FAGA078	91582	80.8	82.6	1.8	-28	4A4		2.45	4.14	37.4					6.59		.63

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAO	PB+ZN	PC+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGA078	91583	82.6	84.0	1.4	-36	404			3.90	6.84	54.5					10.74		.64
FAGA078	91584	84.0	85.3	1.3	-38	4A4			1.68	4.20	28.1					5.88		.71
FAGA078	91585	85.3	86.0	.7	-71	4A0			1.83	3.00	27.1					4.83		.62
FAGA078	91586	262.7	263.9	1.2	-42	4G4			5.10	5.40	64.5					10.50		.51
FAGA078	91587	264.1	264.9	.8	-62	4L42			1.83	3.18	25.4					5.01		.63
FAGA078	91588	265.2	266.7	1.5	-33	4L42			1.23	3.00	20.2					4.23		.71
FAGA078	91589	266.7	267.6	.9	-56	4E4			3.75	6.36	75.8					10.11		.63
FAGA078	91590	284.1	286.1	2.0	-25	4A43			5.25	7.20	89.8					12.45		.58
FAGAC78	91591	286.1	287.4	1.3	-38	4A30			1.50	3.00	20.2					4.50		.67
FAGA078	91592	287.4	289.0	1.6	-31	4A34			1.88	3.24	24.3					5.12		.63
FAGA078	91593	289.0	290.2	1.2	-42	4A34			1.90	3.72	26.1					5.62		.66
FAGAC78	91594	290.2	291.4	1.2	-42	4A30			1.15	1.18	20.2					2.33		.51
FAGAC78	91595	291.4	293.5	2.1	-24	4A34			1.80	4.38	31.2					6.18		.71
FAGAC78	91596	293.5	294.1	.6	-83	4L0			.59	.94	8.2					1.53		.61
FAGA082	91597	97.5	98.3	.8		4D7			2.78	5.04	20.2					7.82		.64
FAGAC82	91598	102.2	103.9	1.7		4C0			1.80	3.06	28.5					4.86		.63
FAGA082	91599	103.9	105.2	1.3		4D0			1.98	3.42	28.5					5.40		.63
FAGA082	91600	118.7	120.7	2.0		4E4			6.15	10.37	91.9					16.52		.63
FAGAC82	91601	121.8	123.4	1.6		4D0			2.08	3.30	44.2					5.38		.61
FAGA082	91602	123.4	124.9	1.5		4D0			2.05	3.12	44.2					5.17		.60
FAGA082	91603	137.1	138.9	1.8		4AE			3.30	6.45	41.5					9.75		.66
FAGA082	91604	273.4	274.1	.7		4G4			4.72	9.40	90.8					14.12		.67
FAGA082	91605	292.2	293.7	1.5		4A4			3.53	4.44	54.5					7.97		.56
FAGA082	91606	293.7	295.2	1.5		4A4			2.23	4.44	33.3					6.67		.67
FAGAC82	91607	320.7	322.2	1.5		4E46			4.92	6.35	72.7					11.27		.56
FAGAC82	91608	327.2	328.7	1.5		4E48			4.28	3.18	45.3					7.46		.43
FAGAC82	91609	328.7	330.3	1.6		4D0			3.98	1.34	40.4					5.32		.25
FAGA082	91610	330.3	331.8	1.5		4E81			1.38	1.86	16.1					3.24		.57
FAGA082	91611	331.8	333.3	1.5		4E81			1.34	1.56	19.2					2.90		.54
FAGA026	92000	128.5	129.5	1.0	100	4A4			3.98	4.20	64.5					8.18		.51
FAGA026	92001	129.5	131.8	2.3	87	4A0			1.50	1.43	28.5					2.93		.49
FAGA026	92002	131.8	134.7	2.9	100	4E1			2.33	2.40	41.5					4.73		.51
FAGA026	92003	134.7	137.8	3.1	100	4E14			4.73	4.02	65.5					8.75		.46
FAGA026	92004	137.8	140.8	3.0	100	4E14			3.08	2.88	48.3					5.96		.48
FAGA026	92005	140.8	143.9	3.1	100	4E1			1.33	2.28	27.4					3.61		.63
FAGA026	92006	143.9	144.8	.9	100	4E14			3.00	3.54	46.3					6.54		.54
FAGA026	92007	144.8	147.1	2.3	26	4E14			2.08	3.48	35.3					5.56		.63
FAGA026	92008	208.7	209.5	.8		4D4			4.95	6.84	80.6					11.79		.58
FAGA026	92009	210.4	211.7	1.3		4D4			4.13	5.52	73.7					9.65		.57
FAGA028	92010	50.6	51.1	.5	80	5D0			.84	.84	15.1					1.68		.50
FAGA028	92011	242.3	244.0	1.7	100	4L15			.12	.09	5.1					.21		.43
FAGA028	92012	248.7	250.2	1.5	100	4L1			.05	.08	1.0					.13		.62
FAGA058	92013	157.0	157.9	.9	89	5C4*			.03	.13	2.1					.16		.81
FAGA058	92014	159.7	160.6	.9	22	4LC			.15	.03	5.1					.18		.17
FAGA058	92015	160.6	164.0	3.4	3	4LC			.22	.46	4.1					.68		.68
FAGA058	92016	164.0	165.8	1.8	78	4L0			.18	.25	1.0					.43		.58
FAGAC65	92017	125.6	126.5	.9	100	4G4			10.50	10.11	115.9					20.61		.49
FAGAC65	92018	126.5	128.0	1.5	40	4G#4			6.00	5.64	74.7					11.64		.48
FAGA065	92019	128.0	128.9	.9	44	4G#4			4.80	2.46	58.6					7.26		.34









DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK	S.G.	CU	PB	ZN	AG	AU	PO	PY	BAO	PB+ZN	PC+PY	ZN
		FROM	TO	M	%	UNIT		%	%	%	G/MT	G/MT	%	%	%	%	%	RATIO
FAGU080	92220	50.3	51.8	1.5	100	4AE4			1.45	3.78	26.4					5.23		.72
FAGUC80	92221	51.8	53.3	1.5	100	4AE4			5.35	5.20	72.7					10.55		.49
FAGU080	92222	53.3	54.9	1.6	100	4AE4			2.78	4.90	39.4					7.68		.64
FAGUC80	92223	54.9	56.4	1.5	100	4AE4			3.05	6.70	50.4					9.75		.69
FAGU080	92224	56.4	57.9	1.5	100	4AE4			3.00	6.98	39.4					9.98		.70
FAGUC80	92225	57.9	59.4	1.5	100	4AE0			1.00	2.53	20.2					3.53		.72
FAGUC80	92226	59.4	60.5	1.1	100	4AE4			3.43	7.80	55.5					11.23		.69
FAGU078	92227	38.1	39.6	1.5	93	4A31			.25	1.20	17.1					1.45		.83
FAGU078	92228	44.2	45.7	1.5	87	4A31			.05	1.00	9.9					1.05		.95
FAGUC78	92229	50.3	51.8	1.5	100	4A31			.05	.62	5.1					.67		.93
FAGU078	92230	56.1	57.6	1.5	100	4A10			.40	.42	26.4					.82		.51
FAGU078	92231	64.0	65.5	1.5	100	4A31			.05	.25	4.1					.30		.83
FAGU078	92232	70.1	71.6	1.5	100	4A31			.06	.37	9.9					.43		.86
FAGUC78	92233	77.7	79.2	1.5	93	4A31			.14	.75	8.2					.89		.84
FAGU078	92234	83.8	85.3	1.5	100	4A31			.11	.55	18.2					.66		.83
FAGUC78	92235	89.9	91.4	1.5	100	4A31			.09	.25	9.9					.34		.74
FAGU078	92236	94.9	96.5	1.6	75	4A31			1.73	2.20	28.5					3.93		.56
FAGU078	92237	96.5	97.8	1.3	100	4A31			.66	1.28	20.2					1.94		.66
FAGU078	92238	97.8	99.4	1.6	94	4A31			.13	.75	9.9					.88		.85
FAGA031	92239	114.6	115.9	1.3	100	4D34			4.95	7.05	68.6					12.00		.59
FAGA031	92240	123.2	124.4	1.2	92	4C37			1.33	1.18	25.4					2.51		.47
FAGA031	92241	133.6	134.4	.8	38	4A0			1.68	1.62	20.2					3.30		.49
FAGA031	92242	134.4	135.9	1.5	93	4A0			1.15	1.35	20.2					2.50		.54
FAGAG31	92243	148.3	148.8	.5	80	4C07			.32	.98	6.2					1.30		.75
FAGA031	92244	168.5	170.3	1.8	94	4E4			4.58	4.86	60.3					9.44		.51
FAGA031	92245	170.3	171.9	1.6	87	4E4			3.90	3.60	44.2					7.50		.48
FAGA031	92246	171.9	172.8	.9	100	4E4			3.38	2.76	39.4					6.14		.45
FAGA031	92247	172.8	174.0	1.2	92	4C3			.64	.34	15.1					.98		.35

NUMBER OF SAMPLES = 9308

ALL ASSAYS

-

DRILL HOLE



















DDH: FAGA010

---DEPTHS---			SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													S.G. W.R.	
FROM	TO	CU %						PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAC %	HG %	MN %	AS %	BA %		
233.6	234.2	11657	.6	.5	400#	3.89		3.79	5.79	138.00		1.23	2	20	.22							
234.2	234.8	11658	.6	.4	400	3.66		1.11	2.89	37.00		2.47	2	18	20							
234.8	235.2	11659	.4	.3	4G4#	4.17		5.70	12.09	180.00		1.16	1	8	9							
235.2	235.5	11660	.3	.3	4A4	3.89		3.60	7.09	76.00		.20	4	13	18							
235.5	236.4	11661	.9	.5	4G4	4.49		3.39	10.80	49.00		.20	1	17	18							
237.5	238.0	11662	.5	.5	4G0	4.28	.04	2.79	5.50	50.00		.34	1	18	20							
239.3	240.0	11663	.7	.6	4G4	4.29	.11	4.20	15.49	91.00		.89	1	17	18							
244.5	245.0	11664	.5	.5	4G4	4.42	.11	5.29	9.59	96.00		.89	1	14	15							
245.5	246.8	11665	1.3	.7	4G4	4.83	.22	6.70	9.69	109.00		1.23	2	21	23							
246.8	247.6	11666	.8	.8	4G4	4.61	.11	4.09	7.59	77.00	73.00	1.16		20	21							
247.6	247.9	11667	.3	.2	4E0	4.67	.08	3.79	5.79	58.99		.75	2	29	32							
247.9	248.4	11668	.5	.5	4C0	3.68	.10	.68	.73	18.00		.27	6	16	22							
156.4	158.3	11700	1.9	1.8	4A0	3.12	.04	1.38	2.39	29.99		1.03	2	8	10							



DDH: FAGA012

						-----ASSAYS-----															
DEPTHS	SAMPLE	INT.	REC.	ROCK	S.G.	CU	PB	ZN	AG(AA)	AG(FA)	AU(FA)	PO	PY	TOT	SAC	HG	MN	AS	BA	S.G.	
FROM	TO	NO.		UNIT	PULP	%	%	%	G/MT	G/MT	G/MT	%	%	FE	%	%	%	%	%	W.R.	
205.4	207.4	14240	2.0	1.9	4A4	.05	2.77	5.70	49.00												
207.4	209.3	14241	1.9	1.8	5D4*	.05	.55	.72	12.00												
209.3	211.1	14242	1.8	1.6	4A0	.02	.28	.66	6.00												
211.1	212.9	14243	1.8	1.5	4A0	.04	.62	1.15	11.00												
212.9	214.3	14244	1.4	1.3	4A0	.05	.78	.69	13.00												
214.3	216.1	14245	1.8	1.8	4A0	.07	.20	.46	3.99												
216.1	218.2	14246	2.1	1.9	4C5	.07	.14	.48	3.99												
218.2	219.7	14247	1.5	1.3	5A19	.10	.40	.70	7.99												
219.7	221.7	14248	2.0	1.9	4C0	.11	.40	.81	7.99												
221.7	222.6	14249	.9	.8	5D4*	.05	.27	.57	6.00												
222.6	224.2	14250	1.6	1.4	4C5	.10	.44	.69	7.99												
224.2	226.0	14251	1.8	1.7	4C0	.10	.57	1.55	12.00												
226.0	227.5	14252	1.5	1.3	4C5	.08	.42	.96	9.00												
227.5	228.9	14253	1.4	1.1	4A0	.05	.44	.88	9.00												
228.9	230.1	14254	1.2	.9	4A4	.04	1.51	4.17	33.00												
256.3	257.9	14255	1.6	1.4	4C5	.02	1.64	2.52	21.00												
257.9	259.7	14256	1.8	1.7	4L27	.05	.36	.62	7.99												
272.7	273.9	14257	1.2	1.2	4C5	2.97	.07	1.19	1.67	21.00		.40	2	4	7						
273.9	276.5	14258	2.6	2.5	4C0	2.89	.02	1.16	2.04	17.00		.89	1	1	3						
276.5	278.0	14259	1.5	1.2	4L12		.02	.64	1.82	12.00											
278.0	279.5	14260	1.5	1.4	4C5		.07	.61	1.90	14.99											
279.5	281.3	14261	1.8	1.7	4A0	3.35	.11	1.40	2.72	29.99		.75	1	15	16						
281.3	283.3	14262	2.0	1.8	4A4	3.25	.11	1.98	3.08	39.00		.89		13	14						
283.3	284.4	14263	1.1	1.0	4C0		.05	.41	.78	13.00											
284.4	286.4	14264	2.0	1.9	4L12		.08	.42	.34	10.00											
286.4	287.5	14265	1.1	1.1	4L12		.05	.05	.17	3.00											
287.5	289.1	14266	1.6	1.5	4L12		.08	1.15	1.17	18.00											
289.1	290.5	14267	1.4	1.3	4A0		.14	.56	.80	17.00											
290.5	292.2	14268	1.7	1.5	4A0		.08	1.71	2.54	29.99											
292.2	294.0	14269	1.8	1.7	4A13		.19	.51	.41	25.00											
294.0	296.1	14270	2.1	2.0	4A13		.19	.63	.36	24.00											
296.1	298.4	14271	2.3	2.2	4A0	3.14	.08	1.18	1.18	25.00		1.33		9	10						
298.4	300.4	14272	2.0	1.9	4A0	3.18	.10	1.30	2.21	27.00		1.23	1	11	13						
300.4	302.4	14273	2.0	1.9	4L12		.05	.39	.27	7.99											
302.4	304.5	14274	2.1	2.0	4A0		.13	.84	1.14	18.00											
304.5	306.2	14275	1.7	1.6	4A0		.08	.98	1.06	17.00											
306.2	308.0	14276	1.8	1.8	4A13		.14	1.78	.40	41.00											
308.0	309.8	14277	1.8	1.7	4A13		.14	.99	.17	26.00											
309.8	311.7	14278	1.9	1.7	4A13		.08	.93	.67	25.00											
311.7	313.5	14279	1.8	1.8	4A13		.14	.34	.29	20.00											
313.5	315.3	14280	1.8	1.6	4A13		.17	.07	.31	15.99											
315.3	317.1	14281	1.8	1.7	4A13		.11	.11	.23	12.00											
317.1	318.4	14282	1.3	1.2	4A13		.16	.04	.23	12.00											
318.4	319.9	14283	1.5	1.2	4G4	4.63	.23	4.95	7.90	102.00		.20		28	29						
319.9	321.3	14284	1.4	1.0	4G4	4.46	.17	3.79	5.50	70.00		.47	1	29	30						
354.5	356.3	14419	1.8	1.1	4E4	4.73	.19	4.19	5.59	59.99		1.16		32	33						
356.3	358.4	14420	2.1	2.1	4E4	4.90	.23	4.38	4.49	69.00		1.16		36	37						
358.4	359.8	14421	1.4	1.4	4G4	4.62	.08	4.50	8.50	79.00		1.16		17	17						
359.8	361.2	14422	1.4	1.1	4EG	4.05	.04	1.87	4.01	41.00		.81	1	23	25						
361.2	362.6	14423	1.4	1.3	4EG	4.67	.11	1.89	6.20	54.00		1.64	19		20						
362.6	363.2	14424	.6	.6	4G4	4.50	.11	3.39	9.09	65.00		1.23		11	12						



















DDH: FAGA023

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														S.G. W.R.
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAC %	HG %	MN %	AS %	BA %	
116.4	118.0	05152	1.6	.0	4A0	3.34	.19	.16	.42	7.00		1.03	3	17	20						
118.0	119.2	05153	1.2	.0	4A0	4.62	.32	1.39	2.09	31.00		1.85	1	37	38						
119.2	119.8	05154	.6	.C	4L0	3.76	.09	1.20	1.53	18.00		1.10	4	27	32						
119.8	121.3	05155	1.5	.0	4E4	3.34	.07	4.59	7.11	64.00		.21	5	8	14						
121.3	122.8	05156	1.5	.0	4E0	2.80	.04	.11	.22	3.00		.07	28	4	32						
122.8	124.7	05157	1.9	.0	4E4	4.45	.27	3.24	4.08	55.00		1.58	4	26	31						
124.7	126.5	05158	1.8	.0	4E0	4.49	.40	1.74	1.50	33.00		1.37	7	29	36						
126.5	128.0	05159	1.5	.0	4A0	4.50	.42	2.76	1.75	38.00		1.23	9	29	38						
128.0	129.5	05160	1.5	.0	4A4	4.60	.21	2.36	3.18	42.00		1.03	6	31	38						
129.5	131.1	05161	1.6	.0	4A0	3.07	.17	.88	1.17	17.00		.41	4	10	15						
131.1	132.6	05162	1.5	.0	4A0	5.19	.27	.60	.35	19.00		.27	13	18	32						
132.6	134.3	05163	1.7	.0	4A0	3.05	.22	.60	.69	14.00		.34	2	10	12						
275.3	277.2	05164	1.9	.0	4A0	3.37	.22	1.95	1.78	32.00		.82									
278.5	280.4	05165	1.9	.0	4A0	3.28	.16	.85	1.05	20.00		.27									
79.9	81.4	90132	1.5	.0	4E4			7.35	12.41	105.90											
221.9	224.3	90134	2.4	.0	4L0			.03	.03		2.10										
245.2	246.9	90135	1.7	.0	4L0			.32	.76		5.10										
134.3	135.8	91074	1.5	.0	4E4	4.51	.12	13.00	20.80	164.00		1.51	1	22	24						
135.8	137.5	91075	1.7	.0	4E4	4.99	.22	6.47	12.70	101.00		1.71	1	31	32						
137.5	139.3	91076	1.8	.0	4A0	3.53	.11	1.83	2.25	33.00		1.17		21	22						
139.3	141.2	91077	1.9	.0	4A4	2.93	.06	2.67	4.50	37.00		.62	1	8	9						

















DDH: FAGA030

						-----ASSAYS-----															
DEPTHS	SAMPLE	INT.	REC.	ROCK	S.G.	CU	PB	ZN	AG(AA)	AG(FA)	AU(FA)	PO	PY	TOT	BAC	HG	MN	AS	BA	S.G.	
FROM	TO	NO.		UNIT	PULP	%	%	%	G/MT	G/MT	G/MT	%	%	FE	%	%	%	%	%	W.R.	
144.5	145.4	06979	.9	.7	4E41	4.05	.10	8.80	17.89	150.00		1.16	3	16	19						
145.4	146.4	06980	1.0	.9	5B21	2.98	.02	.40	.79	11.00		.20	1	3	4						
146.4	148.2	06981	1.8	1.8	4A4	3.12	.02	2.24	5.28	41.00		.68	1	9	10						
148.2	148.7	06982	.5	.3	4A0	3.14	.08	1.51	1.13	38.00		.89		12	13						
148.7	149.7	06983	1.0	1.0	4A1	2.91	.04	.52	1.25	13.99		.47		5	6						
149.7	151.2	06984	1.5	.5	FAULT	2.87	.05	.66	1.28	13.99		4.11		4	5						
151.2	153.7	06985	2.5	2.1	4A1	2.97	.08	1.53	1.41	24.00		.81		6	7						
153.7	155.6	06986	1.9	1.9	4A1	2.91	.05	1.96	2.12	26.00		1.16		3	4						
155.6	157.6	06987	2.0	2.0	4L1	3.08	.05	1.40	2.66	24.00	23.00	.47		3	4						
157.6	158.9	06988	1.3	1.3	5C4a	2.89	.01	.05	.16	3.00		.27	4		4						
158.9	161.3	06989	2.4	.3	4A14	3.08	.05	2.45	5.36	44.00		.75	1	6	8						
161.3	163.0	06990	1.7	1.7	5D4a	3.04	.02	.26	1.37	5.00		.27	5	2	7						
163.0	164.6	06991	1.6	1.5	5D4a	2.99	.02	.95	2.64	19.00		.34	3	2	6						
164.6	165.1	06992	.5	.5	5B46	3.02	.01	.13	.31	1.99		.27	3	1	5						
165.1	165.8	06993	.7	.6	10Q0	2.81	.02	.05	.08	.99		.20	1		2						
165.8	166.4	06994	.6	.6	5B46	2.97	.02	.05	.17	.99		1.23	3	1	5						
166.4	169.0	06995	2.6	2.4	4B4	3.02	.01	3.02	6.99	50.00		.40	3	1	5						
169.0	171.0	06996	2.0	2.0	4B4	3.02	.02	5.13	8.18	92.00		.89	1	1	2						
177.4	179.3	06997	1.9	1.9	4B4	2.87	.02	2.79	4.90	50.00		.47	1		1						
179.3	181.6	06998	2.3	2.1	4B4	2.91	.02	3.39	6.58	59.99		.55	1		1						
181.6	183.3	06999	1.7	1.7	4B4	2.93	.04	3.14	5.62	58.99		.68	1	1	2						
183.3	184.9	07000	1.6	1.6	4B4	2.91	.02	2.33	4.33	44.00		.40	1		2						
184.9	187.5	07101	2.6	2.6	4A14	2.99	.05	3.39	3.29	58.99	54.00	.75		3	4						
187.5	189.8	07102	2.3	2.1	4A14	2.91	.02	2.89	4.20	49.00		.81		1	2						
189.8	190.8	07103	1.0	.2	4L04	2.89	.02	1.56	4.29	28.99		.75	1	1	3						
190.8	192.2	07104	1.4	1.4	4A1	2.85	.01	1.25	3.20	21.00		.55	1		1						
192.2	193.2	07105	1.0	.6	4L0	3.00	.02	.61	1.99	12.00		.34	1		1						
193.2	195.3	07106	2.1	1.6	4A1	2.81	.02	1.03	2.10	19.00		.34		1	2						
195.3	196.9	07107	1.6	1.5	4A14	3.45	.05	2.12	4.40	45.00		.55	1	4	6						
196.9	198.7	07108	1.8	1.8	4A13	3.39	.04	3.00	4.70	54.00		.68	2	14	16						
198.7	200.9	07109	2.2	2.1	4A13	3.76	.07	2.39	.05	46.00		1.16	1	18	19						
200.9	201.6	07110	.7	.5	4A31	4.00	.08	3.60	1.87	70.00		1.37	1	28	30						
201.6	202.0	07111	.4	.3	4A31	3.89	.08	.91	1.62	22.00	18.00	.75	2	25	27						
202.0	202.5	07112	.5	.5	4C0	3.35	.08	2.08	.76	30.99		1.70	1	15	16						
213.8	216.3	07113	2.5	2.3	4D45	3.49	.02	4.79	6.70	83.00		.95	1	13	15						
216.3	217.1	07114	.8	.8	4D4	3.31	.02	4.70	10.90	83.00		1.78	1	8	10						
217.1	217.7	07115	.6	.4	4D45	3.54	.04	6.50	13.59	114.99		1.23	2	10	13						
217.7	219.2	07116	1.5	1.4	4A41	3.24	.04	3.20	6.79	65.00		1.30	1	9	11						
219.2	219.8	07117	.6	.6	4L1	2.95	.02	.20	1.20	3.99		1.03	1	3	5						
219.8	221.5	07118	1.7	1.5	4A4	3.49	.05	6.50	10.00	110.00		1.43	1	11	13						
221.5	222.6	07119	1.1	1.0	4D4	3.79	.02	9.40	16.39	158.00		1.51	2	10	12						
222.6	225.0	07120	2.4	2.4	4A41	3.58	.08	7.40	11.90	110.99		1.30	1	10	11						
225.0	225.7	07121	.7	.5	4A13	3.66	.11	1.74	2.39	29.99	28.99	1.43	2	19	21						
225.7	227.4	07122	1.7	1.5	4L0		.02	.42	.91	7.99											
227.4	231.2	07123	3.8	2.1	4L0		.01	.75	.99	10.00											
254.1	255.3	07124	1.2	1.1	4E4	4.38	.11	3.10	6.70	57.99		1.30	2	27	30						
255.3	255.9	07125	.6	.5	4A4	3.33	.07	5.50	10.19	86.00		1.03	2	5	8						
255.9	257.1	07126	1.2	1.2	4A1	3.43	.08	.88	1.36	17.00		.75	1	13	14						
257.1	257.7	07127	.6	.5	4A4	3.27	.07	4.79	5.59	68.00		1.58	1	10	11						
257.7	261.1	07128	3.4	2.0	4A1	3.12	.08	.56	1.14	14.99		.62	1	11	12						
261.1	263.1	07129	2.0	1.5	4A1	3.35	.10	.34	.95	13.00		.40	1	15	17						

DDH: FAGA030

-----DEPTHS-----		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													S.G. W.R.	
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAG %	HG %	MN %	AS %		BA %
263.1	265.3	07130	2.2	1.4	4A1	3.35	.10	.71	1.32	14.99		1.16	1	12	13						
279.4	281.8	07131	2.4	2.4	4A1		.17	.72	1.31	20.00											
281.8	282.7	07132	.9	.8	5B21		.08	.17	.44	6.99											
282.7	282.9	07133	.2	.2	4A4		.08	5.09	11.50	70.00											
300.8	302.7	07134	1.9	1.5	4L7		.26	1.45	1.10	21.00											
340.5	340.9	07135	.4	.4	4G4S	3.91	.11	5.40	7.49	85.00		1.10	2	12	15						
340.9	342.0	07136	1.1	.9	4L0	2.87	.05	.14	.16	3.99		.20	3	1	5						
342.0	342.7	07137	.7	.6	4E4*	3.58	.13	3.49	3.79	55.99		1.03	4	15	20						





DDH: FAGA038

-----DEPTHS-----				S.G.		-----ASSAYS-----															
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	PULP	CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAC %	HG %	MN %	AS %	BA %	S.G. W.R.
184.6	186.1	08151	1.5	1.5	4HL4	3.52	.11	3.89	5.29	54.00		1.70	1	17	18						
186.1	186.5	08152	.4	.4	4G84	4.25	.13	6.29	6.20	87.00		1.10	3	18	21						
186.5	188.1	08153	1.6	1.4	4AC3	3.64	.13	1.73	2.89	28.99		1.37	2	22	24						
188.1	189.3	08154	1.2	1.2	4AC3	3.58	.19	.69	1.87	13.00		1.10	1	23	24						
189.3	190.5	08155	1.2	1.2	4E4	4.45	.19	4.40	3.70	57.99		2.87	4	30	35						
190.5	191.9	08156	1.4	1.4	4E0	3.47	.16	2.70	1.99	45.00		1.23	1	35	36						
191.9	192.3	08157	.4	.4	5A3	2.98	.01	.17	.11	1.99		1.30	2	1	4						
192.3	194.4	08158	2.1	.9	4C0	3.27	.14	.80	1.88	13.00	14.99	.55	5	7	13						
193.4	195.1	08159	1.7	1.7	4LD7	3.18	.16	.65	1.49	17.00		.55	6	6	13						
215.0	216.4	08160	1.4	1.3	4G0		.10	5.09	4.79	79.00											
225.7	227.4	08161	1.7	1.6	4G4#	4.46	.10	9.50	7.99	108.00		1.10	1	11	13						
227.4	229.2	08162	1.8	1.7	4G4#	4.53	.10	4.59	10.69	73.00		1.03		9	10						
229.2	230.6	08163	1.4	1.3	4G4#	4.37	.14	5.90	6.09	82.00		1.16	2	11	14						
273.7	274.4	08164	.7	.7	4C*7	3.27	.16	1.23	1.47	19.00		.89	6	10	17						
274.4	275.4	08165	1.0	.9	4G4#	4.66	.14	9.90	4.90	121.99		1.37	3	19	23						
275.4	276.8	08166	1.4	1.3	4E0	4.54	.07	3.20	.84	51.00		1.03	1	37	38						
276.8	278.2	08167	1.4	1.4	4E0	4.49	.05	1.54	.90	27.99		1.16	1	35	36						
278.2	279.3	08168	1.1	.8	4G4	4.57	.11	4.50	6.70	73.00		1.10		20	21						
279.3	281.0	08169	1.7	1.7	4A13	3.54	.23	.54	.39	11.00		1.23	1	24	25						
281.0	282.5	08170	1.5	1.4	4A13	3.52	.20	.55	.23	10.00		1.23	1	24	26						
282.5	284.0	08171	1.5	1.4	4G4*	4.50	.17	7.40	9.69	110.00	108.00	1.51	1	21	22						
284.0	286.1	08172	2.1	1.6	4A13	3.49	.19	1.71	1.92	31.99		1.10		17	18						
286.1	288.0	08173	1.9	1.9	4A13	3.14	.08	1.72	.88	28.99		1.23	1	10	11						
288.0	288.6	08174	.6	.5	4E1	4.25	.02	.48	.17	13.00		1.58	1	36	37						
288.6	290.0	08175	1.4	1.4	4A1	3.18	.10	1.42	.80	26.00		2.12	1	11	13						
290.0	291.8	08176	1.8	1.8	4E10	4.04	.08	.79	1.12	20.00		1.23	2	32	35						
291.8	293.4	08177	1.6	1.5	4AG	3.45	.13	3.10	2.04	39.00		1.10	2	15	17						
293.4	295.8	08178	2.4	2.2	4LD7	3.24	.13	1.87	2.29	28.99		.40	7	6	13						
295.8	298.2	08179	2.4	2.4	4LD7	3.54	.20	2.70	2.10	46.00		.40	13	13	26						
341.2	342.1	08180	.9	.9	4G*8	3.62	.20	1.95	1.67	29.99	27.99	.81	5	16	21						
342.1	343.3	08181	1.2	1.2	4A0	2.98	.14	.68	.81	13.99		.62	1	5	6						
343.3	344.1	08182	.8	.7	4G*8	4.05	.17	2.00	1.93	31.99		.95	4	26	31						
344.1	345.6	08183	1.5	1.4	4A1	3.00	.11	.40	.34	6.00		.34	1	3	5						
345.6	346.6	08184	1.0	.9	4L24	3.08	.11	.58	.34	7.99		.40	1	5	7						
346.6	348.2	08185	1.6	1.6	4G*8	3.74	.22	1.87	1.87	38.00		1.03	5	16	21						
348.2	349.8	08186	1.6	1.5	4G*8	4.17	.24	1.57	1.84	31.99		1.30	6	17	23						
349.8	351.5	08187	1.7	1.7	4G*8	4.42	.20	3.27	3.10	45.00		1.23	5	23	29						
351.5	353.5	08188	2.0	2.0	4G*8	3.56	.17	1.45	1.47	34.00		.95	6	15	22						





DDH: FAGA051

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													S.G. W.R.
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAO %	HG %	MN %	AS %	
169.9	172.0	14188	2.1	2.1	4L74		.10	1.02	1.20	17.00										
172.0	173.8	14189	1.8	1.7	4L74		.11	.78	.71	15.99										
173.8	174.8	14190	1.0	.9	4L0		.08	.45	.47	11.00										
203.9	205.7	14191	1.8	1.8	4L74		.05	.56	.54	11.00										
205.7	207.7	14192	2.0	1.9	4L74		.08	.79	.68	14.99										
207.7	209.1	14193	1.4	1.4	4G0	4.48	.14	2.75	2.50	61.99		.75	1	31	33					
209.1	210.4	14194	1.3	1.3	4G4	4.63	.14	6.29	5.20	93.00		.68	3	22	26					
210.4	212.3	14195	1.9	1.8	4C7	3.39	.14	.61	1.38	14.99		.27	4	13	17					
212.3	214.0	14196	1.7	1.7	4C7	3.70	.17	1.85	2.79	28.99		.27	9	13	22					
297.5	299.0	14197	1.5	1.5	4L46	3.16	.05	.63	1.46	12.00		.27	5	4	10					
299.0	300.5	14198	1.5	1.5	4L46	3.47	.05	1.22	1.67	24.00		.47	4	12	17					
300.5	302.1	14199	1.6	1.5	4A0	3.64	.16	1.57	1.60	28.99		.68	3	15	19					
302.1	303.3	14200	1.2	1.2	4A0		.13	.48	.53	13.00										
303.3	305.0	14201	1.7	1.6	4C5		.14	.86	.65	18.00										
307.8	309.7	14202	1.9	1.8	4C5\$		.13	.45	.44	11.00										
309.7	311.2	14203	1.5	1.5	4C5\$		.29	.24	.44	9.00										
311.2	312.8	14204	1.6	1.5	4C5\$		.11	.54	.55	12.00										
312.8	313.8	14205	1.0	1.0	4C\$		.08	1.12	1.08	20.00										
324.9	325.7	14206	.8	.8	4C\$#		.08	1.91	1.71	24.00										
335.3	336.3	14207	1.0	1.0	4C\$		.14	2.22	2.29	35.00										
337.7	338.8	14208	1.1	1.1	4G08		.14	1.73	1.64	28.99										
340.2	341.5	14209	1.3	1.2	4C\$		.14	1.26	1.36	22.00										
341.5	343.2	14210	1.7	1.7	4A\$		.17	.20	.32	7.99										
343.2	345.0	14211	1.8	1.7	4C5\$		.11	.40	.55	9.00										
345.0	346.1	14212	1.1	1.1	4G0\$	4.26	.17	3.16	4.83	43.00		.75	2	17	20					
346.1	347.2	14213	1.1	1.1	4C7\$	3.74	.21	1.56	1.99	26.00		.68	8	17	25					





















DDH: FAGA063

-----DEPTHS-----		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													
FROM	TO						CU %	PE %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAC %	HG %	MN %	AS %	BA %
78.7	80.8	11034	2.1	2.1	4E8*	3.88	.19	1.60	1.38	31.00		.96	22	7	29					
80.8	83.2	11035	2.4	1.8	4D0	3.62	.11	1.77	2.40	30.00		.62	16	5	21					
83.2	85.0	11036	1.8	1.6	4A3		.09	.50	.50	15.00										
85.0	86.9	11037	1.9	1.8	4A3		.19	.38	.27	14.00										
86.9	88.7	11038	1.8	1.8	4A3		.18	.17	.12	13.00										
88.7	90.4	11039	1.7	1.7	4A3		.19	.26	.19	16.00										
90.4	92.2	11040	1.8	1.8	4C*		.18	.12	.16	10.00										
92.2	94.3	11041	2.1	1.6	4A3		.20	.21	.33	12.00										
94.3	96.4	11042	2.1	2.1	4A3		.20	.13	.27	12.00										
96.4	98.4	11043	2.0	1.9	4C0		.30	.36	.72	15.00										
100.1	101.4	11044	1.3	1.3	4E*4	4.10	.40	5.10	7.20	75.00		2.33	29	3	32					
101.4	102.7	11045	1.3	1.3	4E*4	4.62	.32	5.30	6.70	79.00		1.71	27	3	31					
102.7	104.4	11046	1.7	1.7	4G4	4.70	.09	3.80	6.80	74.00		.62	14		15					
104.4	106.1	11047	1.7	1.7	4G4	4.82	.06	4.10	6.80	72.00		.62	20		21					
106.1	107.7	11048	1.6	1.6	4G4	4.67	.06	4.40	6.00	70.00		.69	19		20					
107.7	108.1	11049	.4	.3	4E*	4.82	.16	4.30	6.30	71.00		1.51	36	1	37					
108.1	108.7	11050	.6	.6	4K0	4.45	.04	.64	1.18	18.00		.62	35	2	37					
108.7	109.9	11051	1.2	.5	4E64	4.71	.13	4.90	8.70	79.00		1.58	27	1	28					
109.9	111.2	11052	1.3	.7	4E64	4.05	.04	3.80	6.60	51.00		.55	16	4	20					
111.8	112.9	11053	1.1	.8	4G4	4.62	.06	4.00	6.80	54.00		.48	11	1	13					
113.2	114.1	11054	.9	.9	4D0	3.39	.19	1.68	2.90	25.00		1.03	14	4	19					
114.6	115.4	11055	.8	.7	4E1		.43	.23	.57	14.00										
115.4	117.0	11056	1.6	1.6	4C3		.33	.16	.38	10.00										
117.0	118.7	11057	1.7	1.6	4C3		.19	.16	.42	10.00										
118.7	120.3	11058	1.6	1.6	4C3		.31	.30	.87	14.00										
120.3	120.7	11059	.4	.4	4C*	3.75	.19	1.05	2.40	20.00		.89	22	2	25					
120.7	122.2	11060	1.5	1.3	4C0	3.39	.15	.92	1.90	20.00		.96	9	9	18					
122.2	123.4	11061	1.2	1.1	4C0		.32	.08	.31	11.00										
123.4	125.5	11062	2.1	2.1	4A3		.26	.07	.26	11.00										
125.5	125.9	11063	.4	.3	4A3*		.19	.05	.29	11.00										
125.9	128.0	11064	2.1	2.1	4A3		.30	.09	.32	11.00										
128.0	130.0	11065	2.0	2.0	4A3		.36	.07	.23	10.00										
130.0	130.6	11066	.6	.6	4AD4	3.45	.25	2.40	4.20	34.00		1.10	15	5	20					
98.4	100.1	11067	1.7	1.7	4C34	3.47	.04	2.20	4.30	27.00		.62	13	5	18					
130.6	131.5	11068	.9	.9	4E*4	4.59	.15	4.40	7.20	62.00		1.23	31	2	34					
131.5	132.2	11069	.7	.6	4G4	4.36	.08	5.80	7.00	74.00		.55	17	2	19					
132.8	133.7	11070	.9	.9	4D*		.16	1.20	1.60	16.00										
145.4	147.3	11071	1.9	1.9	4C0	3.64	.10	.97	1.15	15.00		.27	10	6	17					
147.3	147.9	11072	.6	.5	4E*4	4.44	.08	4.30	3.30	38.00		.69	17	4	21					
147.9	149.2	11073	1.3	1.3	4A3		.19	.14	.14	9.00										
149.2	150.5	11074	1.3	1.3	4A3		.15	.13	.19	10.00										
150.5	151.3	11075	.8	.8	4E1		.02	.17	.29	11.00										
151.3	152.6	11076	1.3	1.2	4A3		.36	.05	.12	8.00										
152.6	154.0	11077	1.4	1.3	4A3		.17	.43	.54	13.00										
154.0	155.3	11078	1.3	1.3	4C0		.25	2.30	1.76	33.00										
155.3	156.5	11079	1.2	1.2	4C0	4.47	.10	1.59	2.04	35.00		1.37	25	5	30					
156.5	158.3	11080	1.8	1.7	4A13		.19	.16	.29	9.00										
158.3	159.9	11081	1.6	1.6	4C8		.16	.98	1.14	25.00										
159.9	161.5	11082	1.6	1.6	4C8	4.94	.32	1.67	1.34	32.00		.96	17	12	30					
161.5	163.2	11083	1.7	1.6	4C8	3.83	.17	1.19	1.40	33.00		.75	7	18	25					
163.2	164.8	11084	1.6	1.6	4C8	3.91	.28	1.30	1.48	31.00		.55	8	19	28					













DDH: FAGA068

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAC %	HG %	MN %	AS %	BA %
129.8	130.5	07712	.7	.7	4A43	3.27	.05	2.89	4.70	48.00		1.03	1	11	12					
130.5	131.0	07713	.5	.5	4A31	3.27	.02	.62	.80	15.99		.62		14	15					
131.0	131.7	07714	.7	.7	4L0	3.02	.02	.48	1.23	11.00		.62		8	8					
131.7	132.0	07715	.3	.3	4B4	2.89	.01	2.16	3.29	36.00		.40		2	3					
132.0	133.0	07716	1.0	.9	4A4	3.00	.02	3.20	6.20	59.99		.75	1	3	4					
133.0	133.5	07717	.5	.5	4L0	2.89	.01	.42	1.32	9.00		.34	1	3	5					
133.5	135.5	07718	2.0	1.0	4A0	3.16	.02	1.34	2.79	27.00	24.00	.40		4	4					
135.5	136.3	07719	.8	.8	4L04	2.89	.02	1.66	2.20	27.00		.55		2	3					
136.3	137.4	07720	1.1	1.1	4B4	3.02	.02	4.59	4.09	53.00		1.43		3	4					
137.4	138.9	07721	1.5	1.5	4B4	2.89	.02	2.89	2.29	30.99		.81		2	3					
138.9	140.0	07722	1.1	1.1	4C0	3.04	.05	3.29	.92	34.00		1.23		7	7					
140.0	141.3	07723	1.3	1.3	4C0	2.95	.04	1.80	2.29	30.99		.75	1	4	6					
141.3	141.9	07724	.6	.5	4A14	3.06	.07	3.29	5.90	51.00		.95	1	5	7					
141.9	142.3	07725	.4	.4	5D4*	2.99	.02	.33	1.69	10.00		.47	4	4	8					
142.3	143.0	07726	.7	.5	4A1	3.18	.11	.39	.56	14.99		1.10		14	14					
143.0	143.5	07727	.5	.5	4D0	3.24	.16	2.29	3.49	43.00	42.00	1.30	1	13	14					
143.5	144.0	07728	.5	.4	5C4a	2.93	.02	.49	.70	7.99		.40	5	2	7					
144.0	145.0	07729	1.0	1.0	4D0	3.33	.05	.41	7.59	61.99		.89	1	10	12					
145.0	145.6	07730	.6	.5	4E14	3.62	.02	6.99	14.80	96.00		1.16	3	11	14					
145.6	146.9	07731	1.3	1.3	4A41	3.27	.04	3.39	7.70	56.99		1.03	1	9	11					
146.9	147.4	07732	.5	.4	4D4	3.12	.02	1.97	3.60	33.00		.75	2	7	9					
157.0	158.1	07733	1.1	1.0	4L14	3.52	.17	1.95	3.89	39.00		1.91	1	17	18					
158.1	158.5	07734	.4	.4	4A34	3.02	.05	1.58	3.70	26.00		.75	1	6	7					
163.4	165.5	07735	2.1	2.1	4A1	2.95	.05	1.23	2.08	21.00		.81	1	4	5					
165.5	167.0	07736	1.5	1.5	4A14	2.91	.05	1.95	3.79	31.99		.89		3	4					
167.0	168.9	07737	1.9	1.8	4A1	2.89	.04	1.44	2.39	25.00	26.00	.75		5	6					
168.9	170.7	07738	1.8	1.8	4A1	2.89	.04	1.47	3.00	21.00		1.03		3	3					
170.7	173.1	07739	2.4	2.4	4A13	3.29	.02	2.79	5.40	43.00		1.03	1	11	13					
173.1	175.9	07740	2.8	2.7	4A13	3.41	.05	3.00	5.40	53.00		1.03	1	14	16					
175.9	177.9	07741	2.0	2.0	4A14	2.93	.04	1.42	3.99	25.00		.81	1	4	5					
177.9	179.7	07742	1.8	1.8	4A14	2.93	.05	2.19	3.89	30.99		.89		3	3					
179.7	181.6	07743	1.9	1.9	4A14	2.91	.02	1.25	4.09	21.00		.81	1	2	3					
181.6	183.3	07744	1.7	1.7	4A14	2.95	.02	1.77	3.60	40.00		.62		2	3					
183.3	185.3	07745	2.0	2.0	4A14	3.10	.02	1.90	5.29	42.00		.81	1	3	5					
185.3	187.3	07746	2.0	1.8	4A14	3.41	.05	5.00	6.40	74.00		1.23	1	10	12					
187.3	188.7	07747	1.4	1.4	4D0	3.35	.10	3.99	2.16	53.00	50.00	1.51	1	16	17					
190.2	191.4	07748	1.2	1.2	4D45	3.58	.02	6.29	13.50	95.00		1.16	2	11	13					
191.4	192.9	07749	1.5	1.2	4D45	3.52	.02	4.59	10.59	75.00		1.37	1	12	14					
192.9	193.4	07750	.5	.5	4A1	3.45	.02	.99	3.49	22.00		.89	2	16	18					
199.9	201.7	07751	1.8	1.5	4D4	3.37	.05	5.20	5.50	71.00		1.03	2	8	11					
201.7	203.5	07752	1.8	1.8	4A13		.17	.46	1.07	13.99										
208.0	209.7	07753	1.7	1.7	4A0	3.18	.11	1.92	2.17	29.99		1.78	2	7	10					
209.7	210.6	07754	.9	.8	4L0	2.95	.01	.04	.07	5.00		.20	3	2	5					
210.6	212.3	07755	1.7	1.7	4A14	3.31	.11	2.70	2.89	39.00		1.64	1	12	13					
212.3	213.7	07756	1.4	1.3	4A1	3.64	.22	1.51	3.29	42.00		2.54	1	20	22					
213.7	215.3	07757	1.6	1.4	4A1	3.39	.14	1.23	3.39	30.99		1.78	1	15	16					
222.5	223.5	07758	1.0	1.0	4K4	3.29	.08	3.29	6.79	66.00	60.99	.47	6	7	14					
223.5	224.0	07759	.5	.4	4D4	3.56	.02	5.00	8.50	90.00		1.51	2	11	13					
224.0	225.5	07760	1.5	1.5	4A14	3.43	.11	4.20	5.00	61.99		1.85	2	12	14					
244.0	245.7	07761	1.7	1.7	4A13	3.18	.08	1.97	2.60	26.00		.89	1	9	11					
245.7	247.5	07762	1.8	1.7	4A13	3.24	.08	1.12	1.55	25.00		.75	1	12	14					



DDH: FAGA069

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PC %	PY %	TOT FE	BAC %	HG %	MN %	AS %	BA %	S.G. W.R.
213.2	215.8	07951	2.6	2.1	4K4	3.27	.02	2.89	5.00	52.00		.62	3	6	10						
215.8	217.8	07952	2.0	2.0	4K0	3.37	.02	.68	2.20	20.00		.47	1	14	16						
217.8	219.9	07953	2.1	2.1	4K4	3.35	.02	2.60	6.59	35.00		.55	3	8	12						
222.1	222.5	07954	.4	.4	4A0	3.02	.02	1.32	2.70	21.00		1.30	2	3	6						
232.2	234.1	07955	1.9	1.9	4A14	3.49	.11	3.10	4.90	51.00		2.12	1	16	17						
237.7	239.4	07956	1.7	1.6	4A14	3.08	.14	3.70	5.20	63.99	62.99	1.51	1	10	11						
239.4	240.4	07957	1.0	1.0	5B69	2.89	.01	.41	1.74	7.99		.47	2		3						
241.8	243.4	07958	1.6	1.6	4A10	3.00	.08	1.39	2.50	23.00		1.03	1	4	5						
304.6	305.1	07959	.5	.5	4A10	3.10	.07	.66	1.11	17.00		1.23		10	11						
305.1	306.8	07960	1.7	1.6	4G4#	4.45	.14	5.09	10.40	91.00		2.06	1	21	22						
306.8	307.8	07961	1.0	.9	4E4	4.45	.31	3.10	3.70	55.99		2.66	1	32	33						
307.8	308.5	07962	.7	.5	4G4#	4.59	.17	5.40	7.49	95.00		2.25		29	29						
308.5	309.4	07963	.9	.9	4E4	4.45	.17	3.99	3.39	56.99		1.98	1	31	33						
309.4	309.8	07964	.4	.4	4G4#	4.57	.24	7.70	8.40	116.99		3.08		28	29						
309.8	310.7	07965	.9	.9	4E4#	4.58	.26	4.90	5.90	78.00		2.54		33	34						
310.7	312.4	07966	1.7	1.7	4E4#	4.23	.17	3.60	4.09	72.00	59.99	1.58		32	33						
315.5	317.3	07967	1.8	1.7	4A14	3.18	.07	2.60	3.49	40.00		1.30	1	13	14						
317.3	320.3	07968	3.0	3.0	4A14	3.22	.05	2.70	3.39	41.00		1.43		8	9						
320.3	323.1	07969	2.8	2.8	4A10	3.20	.10	1.01	1.14	26.00		1.23		14	15						
323.1	326.3	07970	3.2	3.2	4A10	3.04	.08	.40	.48	14.99		.81		14	14						
352.5	353.9	07971	1.4	1.4	4LH	3.64	.17	2.39	2.60	33.00		.27	10	16	27						
353.9	355.2	07972	1.3	1.3	4LH	3.41	.14	2.50	2.20	31.99		.14	9	14	24						
234.1	236.0	07973	1.9	1.9	4A10	3.14	.08	1.81	2.60	34.00		1.23	1	11	12						
138.6	139.1	08359	.5	.5	4C0		.19	.77	1.05	24.00											
139.1	140.1	08360	1.0	1.0	4A3	3.58	.14	.34	.36	13.00		.68	1	22	24						
140.1	140.7	08361	.6	.5	4D4	3.91	.23	6.29	5.09	100.00		2.06	2	20	23						
140.7	142.5	08362	1.8	1.7	4C3	4.01	.24	.46	.55	23.00		1.43	2	29	32						
142.5	143.9	08363	1.4	1.2	4A3	3.49	.11	1.07	1.54	27.99	27.99	1.58	1	19	21						
144.3	146.6	08364	2.3	2.2	4A4	3.41	.08	3.89	6.00	68.00		1.58	1	12	14						
146.6	148.3	08365	1.7	1.7	4A4	3.76	.19	2.50	4.90	45.00		1.37	1	16	18						
148.3	149.4	08366	1.1	1.0	4A0	3.43	.11	1.10	1.89	27.00		1.70		17	17						
149.4	151.2	08367	1.8	1.8	4A4	3.24	.04	1.97	3.49	37.00		.81		9	10						
151.2	153.0	08368	1.8	1.8	4L0	2.97	.02	.32	.59	6.00		.55	1	1	2						
153.0	154.8	08369	1.8	1.8	4A10	2.98	.02	.68	.47	11.00		.68		5	6						
154.8	157.1	08370	2.3	2.2	4A10	2.93	.04	.58	.58	7.99		.75		5	5						
157.1	159.1	08371	2.0	2.0	4A10	2.93	.02	.93	1.79	18.00		.68		1	1						
159.1	160.8	08372	1.7	1.6	4L4	3.04	.04	1.62	1.99	27.99		.68	1	2	4						
162.2	162.7	08373	.5	.5	4L24		.23	.39	1.26	9.00											
162.7	164.8	08374	2.1	2.1	4A10		.13	.80	1.69	20.00											
164.8	166.7	08375	1.9	1.9	4A10		.08	.24	.47	6.00											
166.7	168.4	08376	1.7	1.7	4A10		.08	.40	.90	7.99											
168.4	168.9	08377	.5	.4	5C4*	3.12	.02	1.43	5.70	23.00	24.00	.40	4	2	6						
168.9	170.0	08378	1.1	1.1	4A14	3.37	.04	1.84	4.59	34.00		1.10	1	12	13						
170.0	170.7	08379	.7	.7	4L24	3.27	.05	.46	1.03	9.00		.34	3	5	8						
172.2	174.0	08380	1.8	1.8	4A14	3.27	.10	2.39	4.40	39.00		1.03	1	8	10						
174.0	175.9	08381	1.9	1.8	4A10	3.12	.10	1.73	1.89	28.99		.95	1	5	6						
175.9	177.5	08382	1.6	1.6	4A10	3.10	.05	1.13	1.87	22.00		.75		5	6						
177.5	179.3	08383	1.8	1.7	4A14	3.10	.02	1.94	4.79	38.00		.55	1		1						
179.3	181.1	08384	1.8	1.8	4A10	2.95	.02	1.45	3.00	27.99		.40			1						
181.1	183.5	08385	2.4	1.8	4A10	3.08	.02	1.40	2.60	25.00		.40			1						
183.5	184.8	08386	1.3	1.3	4A10	2.98	.02	1.36	2.04	21.00		.81		1	1						



























DDH: FAGA080

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PC %	PY %	TOT FE	BAG %	HG %	MN %	AS %	BA %	S.G. W.R.
264.9	266.7	11967	1.8	1.7	4A0	2.98	.04	.51	1.55	10.00		.14	6	6	12						
266.7	268.2	11968	1.5	1.5	4A0	2.98	.04	1.01	1.99	20.00		.20	3	6	9						
268.2	270.1	11969	1.9	1.8	4A0	2.93	.02	.97	1.84	18.00		.27	2	5	8						

DDH: FAGA081

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PC %	PY %	TOT FE	BAC %	HG %	MN %	AS %	BA %
54.6	56.7	08514	2.1	2.1	4L2	3.39	.11	1.85	2.60	27.00		.34	5	10	15					
56.7	57.8	08515	1.1	1.1	4E*8	3.99	.16	2.70	2.40	42.00		1.03	6	26	32					
57.8	59.3	08516	1.5	1.4	4A3	3.56	.20	.19	.30	13.00		.82	2	23	25					
59.3	60.4	08517	1.1	.9	5D1*	3.10	.05	.27	.65	8.00		.41	4	6	10					
60.4	61.9	08518	1.5	.9	4E1	3.98	.41	.45	.44	18.00		.89	1	29	30					
61.9	63.4	08519	1.5	.7	4E1	4.30	.43	5.50	6.60	76.00		1.17	1	26	27					
63.4	64.3	08520	.9	.9	4E*4	4.91	.12	13.60	11.80	179.00		1.17	1	24	25					
64.3	65.7	08521	1.4	.5	4L31	3.60	.28	1.72	1.96	31.00	33.00	1.51	3	18	21					
65.7	67.1	08522	1.4	.9	4L31	3.45	.19	1.08	.87	19.00		.27	2	18	20					
67.1	68.3	08523	1.2	1.1	4E4	4.69	.18	9.40	10.30	126.00		1.23	3	26	29					
68.3	69.6	08524	1.3	.5	4E4	4.78	.19	5.70	7.40	77.00		.48	2	32	35					
69.6	71.1	08525	1.5	1.0	4E*4	4.69	.01	.15	.19	6.00		1.23	3	28	32					
173.2	173.8	08526	.6	.5	4E0	4.14	.32	8.80	8.40	122.00		.27	6	30	37					
173.8	174.3	08527	.5	.5	4C*	3.57	.15	1.26	1.63	27.00		.07	4	16	23					
174.3	175.6	08528	1.3	1.3	4C*	3.64	.16	1.99	2.40	32.00		.55	6	17	24					
175.6	176.9	08529	1.3	1.3	4C*	3.55	.12	1.88	2.10	29.00		.75	5	15	21					
176.9	177.8	08530	.9	.9	4L1	3.27	.08	1.17	1.58	21.00		.34	5	10	15					
184.3	185.8	08531	1.5	1.5	4E*4	3.54	.12	2.06	2.80	32.00	38.00	1.03	5	15	21					
185.8	187.5	08532	1.7	1.7	4E*4	3.45	.10	2.09	2.30	32.00		.55	6	12	18					
188.1	190.3	08533	2.2	2.1	4E*1	3.43	.07	1.85	2.40	25.00		.34	6	10	17					
190.3	192.4	08534	2.1	2.1	4E*1	3.29	.08	1.67	1.84	23.00		.41	4	8	12					
192.4	193.1	08535	.7	.7	4A3	3.45	.12	1.86	2.50	29.00		.41	6	12	19					

























DDH: FAGA092

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAC %	HG %	MN %	AS %	BA %	S.G. W.R.
49.4	51.5	09257	2.1	1.2	4D0	3.45	.04	3.70	4.20	56.00		.48	4	14	18						
51.5	53.8	09258	2.3	2.2	4D4	3.57	.04	10.10	12.80	135.00		1.03	3	9	13						
53.8	55.7	09259	1.9	1.2	4D4	3.77	.04	5.90	9.60	92.00	96.00	.89	2	13	15						
55.7	56.7	09260	1.0	.7	4A4	3.56	.18	8.10	14.30	123.00		1.51	5	8	13						
189.6	190.8	09261	1.2	1.2	4G4*	3.45	.05	4.80	7.60	79.00		.55	2	8	10						
190.8	192.2	09262	1.4	1.2	4CD	3.49	.14	3.00	2.80	50.00		1.23	1	18	19						
192.2	193.0	09263	.8	.8	4G4*	4.50	.22	11.50	10.10	173.00		2.67	1	24	25						
193.0	194.4	09264	1.4	1.4	4L2	3.16	.05	1.31	1.72	36.00		.69	2	9	11						



DDH: FAGA095

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PC %	PY %	TOT FE	BAC %	HG %	MN %	AS %	BA %	S.G. W.R.
57.0	57.9	06129	.9	.6	4A4	3.43	.05	4.99	8.99	75.00		1.10	1	12	14						
57.9	58.8	06130	.9	.9	4D4	4.00	.06	11.20	20.00	160.00		1.78	1	15	16						
58.8	60.4	06131	1.6	.9	4LD	3.14	.02	2.41	4.48	44.00		.62		8	8						
60.4	61.6	06132	1.2	.9	4A4	3.15	.02	2.20	3.17	36.00		.89		8	9						
61.6	63.0	06133	1.4	1.0	4DE4	3.97	.12	5.24	8.75	98.00		1.23	1	18	19						
63.0	63.8	06134	.8	.6	4LD	3.26	.04	3.43	6.66	52.00		.41	4	5	9						
63.8	65.4	06135	1.6	1.6	4A4	3.44	.10	4.46	8.18	75.00	74.00	.96	1	14	15						









DDH: FAGA100

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAC %	HG %	MN %	AS %	BA %
65.4	66.2	11453	.8	.8	4G4*	4.50	.06	10.30	11.30	190.00		.96	1	19	21					
67.4	68.7	11454	1.3	1.3	4G4*	4.35	.03	10.50	12.60	183.00		1.03	1	19	21					
68.7	70.1	11455	1.4	.9	4K4	3.65	.02	3.50	5.40	52.00		.41	1	14	16					
71.1	72.1	11456	1.0	1.0	4G4*	4.45	.03	12.90	13.50	195.00		.69	1	20	21					
72.1	72.5	11457	.4	.4	4K4	3.62	.06	4.20	6.60	86.00		.69	1	13	15					
72.5	73.5	11458	1.0	.9	4G4*	4.31	.12	11.10	11.50	184.00		1.71	1	18	20					
81.3	82.7	11459	1.4	.7	4G4*	4.37	.05	5.90	8.70	99.00		.69	2	15	18					
88.8	89.6	11460	.8	.5	4D46	4.13	.06	9.00	8.30	131.00		.27	1	12	14					
90.9	91.4	11461	.5	.5	4G4*	4.21	.07	7.00	9.10	114.00		.69	4	9	13					
91.4	92.1	11462	.7	.7	4E4*	4.69	.08	9.40	8.40	132.00	129.00	1.65	1	24	26					
92.1	93.5	11463	1.4	1.3	4D0	3.96	.15	3.10	3.60	50.00		1.17	2	17	19					
93.5	94.1	11464	.6	.6	4L14	3.04	.05	.45	.73	9.00		.21	2	3	6					
174.7	176.5	11465	1.8	1.0	4G4*	4.19	.03	6.40	10.80	103.00		.27	1	19	20					
176.5	178.3	11466	1.8	1.8	4G4*	4.70	.11	7.00	10.70	119.00		.62		13	14					
178.3	180.0	11467	1.7	1.4	4E41	4.86	.08	2.80	4.40	53.00		1.03	1	35	36					
180.0	181.7	11468	1.7	1.4	4E41	4.81	.09	3.90	5.90	66.00		1.03	1	34	36					
181.7	184.1	11469	2.4	1.2	4A4	3.35	.06	3.40	6.10	54.00		.96	1	11	12					
184.1	185.0	11470	.9	.5	4A4	3.09	.04	2.50	4.00	45.00		.55	1	4	6					
185.0	185.4	11471	.4	.4	4A4	3.23	.03	4.70	7.40	76.00		.48	2	3	5					
185.4	187.2	11472	1.8	1.6	4A0	3.00	.02	.37	.69	7.00	8.00	.27	2	2	4					
187.2	189.0	11473	1.8	1.7	4A0	3.04	.03	.36	.31	7.00		.07	3	3	6					

DDH: FAGA102

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													S.G. W.R.	
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAO %	HG %	MN %	AS %		BA %
137.0	139.4	09788	2.4	2.4	4A0	3.01	.04	1.40	2.10	23.00		.69	2	5	8						
139.4	140.5	09789	1.1	1.1	4E4	4.23	.13	8.40	8.10	106.00		1.65	5	22	27						
140.5	142.0	09790	1.5	1.5	4E0	4.14	.39	.96	1.25	25.00		1.30	2	33	35						

DDH: FAGA103

						-----ASSAYS-----															
---DEPTHS---	SAMPLE	INT.	REC.	ROCK	S.G.	CU	PB	ZN	AG(AA)	AG(FA)	AU(FA)	PO	PY	TOT	BAC	HG	MN	AS	BA	S.G.	
FROM	TO	NO.		UNIT	PULP	%	%	%	G/MT	G/MT	G/MT	%	%	FE	%	%	%	%	%	W.R.	
136.8	138.8	09777	2.0	2.0	4A0	.11	.23	.73	7.00												
138.8	140.8	09778	2.0	1.8	4A0	.10	.07	.15	3.00												
140.8	142.8	09779	2.0	1.9	4A0	2.98	.04	.21	.71	5.00		.55	3	4	8						
142.8	144.6	09780	1.8	1.6	4A0	2.86	.03	2.93	4.30	36.00		.89	1	2	4						
144.6	145.1	09781	.5	.5	4K4*	3.48	.09	2.93	4.10	47.00	45.00	.69	4	16	20						
147.0	148.6	09782	1.6	.0	4A0	2.98	.05	1.06	2.20	22.00		.55	2	4	7						
160.0	160.9	09783	.9	.9	4E4*	4.29	.12	4.80	5.90	62.00		1.51	4	26	31						
160.9	162.0	09784	1.1	1.1	5D4	2.92	.03	.21	.20	3.00		.27	5	1	6						
162.0	162.8	09785	.8	.8	4E46	4.67	.02	3.60	5.00	35.00		.75		35	36						
162.8	163.8	09786	1.0	.9	4G4*	4.50	.03	2.61	5.70	28.00		.75	1	25	27						
170.3	171.9	09787	1.6	1.1	4G4*	3.92	.04	5.30	7.00	83.00		1.10	1	8	9						

DDH: FAGA104

---DEPTHS---			SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													S.G. W.R.
FROM	TO	CU %						PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PC %	PY %	TOT FE	BAC %	HG %	MN %	AS %	BA %	
103.1	104.5	14614	1.4	1.4	4A41	3.18	.05	2.31	4.25	40.00		.27	2	9	11						
105.3	107.8	14615	2.5	2.2	4A41	3.14	.02	1.92	4.25	36.00		.14	2	7	10						
107.8	109.5	14616	1.7	1.7	4D0	3.12	.08	2.00	3.64	34.00		.07	4	6	10						
118.5	120.5	14617	2.0	1.4	4AD	3.24	.04	4.29	6.79	71.00		.27	2	6	9						
120.5	122.5	14618	2.0	1.8	4AD	3.02	.04	2.62	4.11	43.00		.20	1	4	6						
122.5	124.5	14619	2.0	1.6	4AD	3.00	.02	1.07	2.43	19.00		.07	2	4	6						
124.5	126.5	14620	2.0	1.3	4AD	2.98	.02	1.53	3.08	23.00		1.37	2	2	5						
126.5	127.8	14621	1.3	.9	4LD	3.02	.05	1.87	3.31	27.00		.01	2	3	6						
127.8	129.8	14622	2.0	1.8	4AD	3.02	.02	.94	2.46	13.99		.14	6	1	7						
129.8	131.8	14623	2.0	2.0	4AD	3.08	.14	1.60	3.93	38.00		.14	2	7	9						
131.8	133.6	14624	1.8	1.7	4AD	3.08	.04	2.06	5.09	29.99		.14	4	3	7						
133.6	135.6	14625	2.0	1.9	4D0	2.99	.02	2.64	6.40	40.00		.07	3	2	5						
135.6	137.6	14626	2.0	1.9	4D4	3.00	.02	2.79	7.29	52.00		.47	1	3	4						
137.6	139.6	14627	2.0	1.8	4D0	3.00	.04	2.04	4.21	36.00		.34	2	4	7						
139.6	141.6	14628	2.0	1.9	4D4	3.22	.14	3.08	7.70	53.00		1.91	2	7	10						
141.6	143.6	14629	2.0	1.9	4D0	3.08	.05	3.16	4.32	45.00		.40	3	5	8						
143.6	145.6	14630	2.0	2.0	4D0	3.08	.08	4.00	5.70	67.00		.40	3	3	7						
145.6	147.6	14631	2.0	2.0	4D0	3.00	.02	2.91	5.29	43.00		.68	2	2	4						
147.6	150.1	14632	2.5	2.5	4D0	3.18	.04	2.18	5.59	36.00		.01	2	3	6						
150.1	151.5	14633	1.4	1.4	4C5E	3.29	.02	.93	3.04	18.00		.89	1	11	13						
151.8	153.8	14634	2.0	1.8	4AC	3.02	.02	.69	1.53	13.99		.47	3	13	16						
153.8	155.8	14635	2.0	1.6	4A10	2.99	.10	1.53	1.63	27.00		.75		8	8						
155.8	157.8	14636	2.0	1.7	4A14	3.16	.05	1.94	3.39	30.99		.68	1	5	6						
157.8	160.4	14637	2.6	2.5	4A10	4.00	.02	1.81	3.06	27.00		1.51	1	9	11						
161.3	162.3	14638	1.0	.8	4EC	3.33	.28	2.22	2.68	45.00		1.10	1	27	29						
162.3	164.3	14639	2.0	1.9	4A14	3.20	.07	2.66	4.19	37.00		.89	1	12	14						
164.3	166.3	14640	2.0	2.0	4A14	3.02	.02	3.00	5.20	49.00		.68	1	8	9						
166.3	168.3	14641	2.0	1.7	4A14	2.91	.02	2.08	4.84	35.00		.62	1	4	5						
168.3	171.0	14642	2.7	2.3	4A10	2.95	.02	1.71	2.18	23.00		.75	1	1	2						
199.4	202.8	14643	3.4	3.1	4A41	3.41	.05	5.09	8.80	85.00		1.30	1	11	12						
202.8	204.8	14644	2.0	2.0	4A14	3.12	.05	3.10	4.41	44.00		.75	1	7	9						
204.8	206.7	14645	1.9	1.9	4A14	3.02	.02	2.02	4.51	28.99		.81	2	2	4						
362.2	364.2	14646	2.0	1.5	4ACE		.08	.47	.67	11.00											
364.2	366.2	14647	2.0	1.8	4ACE		.10	.28	.41	6.99											
366.2	368.7	14648	2.5	2.5	4ACE	3.62	.14	1.32	1.98	22.00		.95	2	19	21						
391.6	393.1	14649	1.5	1.4	4G4	4.62	.16	5.09	8.50	92.00		.75		10	11						
393.1	394.8	14650	1.7	1.4	4AD	3.06	.07	1.45	2.81	26.00		.81	1	5	6						
401.0	403.0	14651	2.0	2.0	4ED	4.21	.17	1.99	2.18	27.99		1.10	3	24	28						
403.0	404.5	14652	1.5	1.1	4ED	4.54	.36	2.18	2.85	36.00		1.51	11	27	38						
404.5	407.5	14653	3.0	2.9	4GEL	3.70	.11	3.99	5.20	69.00		1.85	2	11	14						





















DDH: FAGA116

-----DEPTHS----		SAMPLE NO.	INT.	REC.	ROCK UNIT.	S.G. PULP	-----ASSAYS-----													
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PG %	PY %	TOT FE	BAG %	HG %	MN %	AS %	BA %
110.9	112.5	09397	1.6	1.6	4A13	3.16	.05	1.60	3.08	29.00		.75	1	10	11					
112.5	114.1	09398	1.6	1.6	4A13	3.13	.03	1.50	3.18	27.00		.55	1	7	8					

DDH: FAGA117

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													S.G. W.R.		
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAC %	HG %	MN %	AS %		BA %	
80.8	81.2	09405	.4	.4	4G4	4.47	.18	5.60	11.50	100.00		1.37	1	20	21							
81.2	83.1	09406	1.9	1.9	4D4	4.18	.14	12.30	19.60	210.00	220.00	2.26	2	10	12							
83.1	85.2	09407	2.1	2.1	4A4	3.66	.06	8.70	19.00	171.00		1.10	3	7	10							
85.2	86.0	09408	.8	.7	4E14	4.17	.13	9.90	19.60	206.00		2.13	2	13	16							
86.0	87.8	09409	1.8	1.8	4E4	4.66	.22	6.00	8.50	104.00		1.65	1	28	30							
87.8	89.6	09410	1.8	1.8	4G4	4.61	.18	5.90	10.90	103.00		1.51	1	14	16							
97.1	97.4	09411	.3	.3	4G4	4.45	.05	3.50	7.30	76.00		1.03	1	11	12							
97.4	98.1	09412	.7	.7	4E64	4.81	.18	4.70	8.60	102.00		1.03	2	23	25							
99.1	101.2	09413	2.1	2.1	4E*4	4.63	.24	5.10	8.70	102.00		.96	1	31	33							
101.2	103.3	09414	2.1	2.1	4E*4	4.37	.18	4.50	6.50	86.00		1.03	1	26	28							
150.3	150.9	09415	.6	.6	4D4	3.56	.13	4.20	4.90	70.00		1.71	1	13	14							
151.3	152.4	09416	1.1	1.1	4D74	3.69	.22	3.70	6.00	63.00	66.00	2.88	5	13	18							
152.4	153.8	09417	1.4	1.4	4C0	3.36	.27	.82	1.59	42.00		1.44	3	14	17							
153.8	155.2	09418	1.4	1.4	4C0	3.46	.20	1.20	1.26	30.00		2.26	2	18	20							
155.2	156.4	09419	1.2	1.2	4D4	3.66	.14	5.30	5.90	81.00		1.92	2	16	19							
156.4	157.9	09420	1.5	.3	4D4	3.75	.15	6.40	11.90	101.00		2.54	3	12	15							







DDH: FAGA120

						-----ASSAYS-----															
---DEPTHS---	SAMPLE	INT.	REC.	ROCK	S.G.	CU	PB	ZN	AG(AA)	AG(FA)	AU(FA)	PO	PY	TOT	BAO	HG	MN	AS	BA	S.G.	
FROM	TO	NO.		UNIT	PULP	%	%	%	G/MT	G/MT	G/MT	%	%	FE	%	%	%	%	%	W.R.	
384.9	387.3	12899	2.4	2.4	4A7\$	.11	.05	.10	3.00												
387.3	389.7	12900	2.4	2.3	4A7\$	.10	.11	.13	5.00												
389.7	390.4	12901	.7	.7	4C5\$	.11	1.42	1.72	29.99												
390.4	391.1	12902	.7	.7	4A79	.08	.05	.05	3.99												
392.1	393.9	12903	1.8	.9	4ADE	.10	2.56	3.91	45.00												
403.8	405.1	12904	1.3	1.2	4EG@	4.25	.08	5.00	7.90	75.00		.75	16	2	18						
405.1	407.5	12905	2.4	2.4	4E8	4.61	.34	1.16	1.15	27.00		1.23	26	11	38						
407.5	408.5	12906	1.0	.9	4G4\$	4.34	.16	4.57	6.70	65.00		1.51	13	3	16						



DDH: FAGA122

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PC %	PY %	TOT FE	BAC %	HG %	MN %	AS %	BA %
120.6	122.2	07029	1.6	1.5	4G4	4.16	.09	4.30	8.90	74.00		.89	1	25	27					
122.2	123.0	07030	.8	.8	4DE	4.60	.22	5.90	7.60	133.00	127.00	.55		28	29					
135.4	137.8	07031	2.4	2.4	4A3		.10	.18	.36	12.00										
137.8	140.3	07032	2.5	2.5	4A3		.11	.70	1.12	16.00										
140.3	141.0	07033	.7	.7	4E08		.29	.75	.70	27.00										
141.0	143.5	07034	2.5	1.6	4A3		.12	.09	.16	9.00										
143.5	146.0	07035	2.5	1.4	4A3		.05	.15	.23	7.00										
146.0	148.5	07036	2.5	1.6	4A3		.08	.20	.19	10.00										
148.5	150.0	07037	1.5	1.5	4LC		.13	.19	.60	8.00										
160.6	163.5	07038	2.9	2.9	4A31		.05	.03	.03	4.00										
163.5	166.4	07039	2.9	1.5	4A31		.02	.04	.13	4.00										
166.4	169.2	07040	2.8	1.4	4A31		.01	.03	.02	4.00										
169.2	172.0	07041	2.8	2.4	4A31		.03	.01	.01	4.00										
199.0	202.1	07042	3.1	2.3	4A31		.06	.13	.12	6.00										
202.1	203.0	07043	.9	.9	4G48	4.45	.11	4.60	5.50	73.00		.41	13	14	27					
203.0	203.5	07044	.5	.5	4A31	2.88	.09	.10	.07	5.00		.21	3	27	30					
203.5	206.0	07045	2.5	2.4	4EG8	4.02	.25	3.15	2.78	43.00		.96	7	26	34					
206.0	208.6	07046	2.6	2.6	4CG8	4.33	.27	2.70	1.91	41.00		1.17	8	17	25					
208.6	211.2	07047	2.6	2.6	4CG8	3.69	.27	2.62	2.02	37.00		1.65	7	18	26					
211.2	213.7	07048	2.5	2.5	5B23	2.86	.03	.07	.03	3.00		.14	1	1	3					
213.7	214.1	07049	.4	.4	4L23	3.02	.10	.55	.23	12.00		.62	3	3	6					
214.1	216.4	07050	2.3	2.3	4EG8	3.93	.14	2.02	1.94	38.00		1.10	7	23	30					
216.4	218.6	07051	2.2	2.2	4EG8	4.45	.21	3.97	3.10	55.00		1.23	8	26	34					
218.6	220.8	07052	2.2	2.2	4EG8	4.21	.17	1.68	1.35	33.00	32.00	1.65	8	22	31					
220.8	221.6	07053	.8	.5	5A1	2.91	.09	.30	.21	9.00		.55	2	3	5					
221.6	222.1	07054	.5	.3	4EG4	4.40	.07	3.50	5.10	56.00		1.03	4	29	34					
222.1	222.6	07055	.5	.4	4B0	2.93	.15	1.85	6.90	43.00		1.23	1	3	4					

























DDH: FAGA137

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													S.G. W.R.	
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAG %	HG %	MN %	AS %		BA %
96.3	97.7	09C06	1.4	1.4	4A4		.06	2.30	4.60	39.00											
102.9	104.4	09C07	1.5	1.5	4D4	3.76	.07	4.20	6.90	74.00		.89	2	8	10						
104.4	106.6	09C08	2.2	2.2	4A13	2.99	.06	1.71	2.90	30.00		.75		6	7						
106.6	108.7	09C09	2.1	2.1	4A13	3.31	.05	1.54	3.50	31.00		.69		15	16						
108.7	110.8	09C10	2.1	2.1	4A13	3.31	.04	1.20	2.60	29.00	26.00	.62		3	4						
110.8	112.9	09C11	2.1	2.1	4A13	2.94	.04	.62	.97	18.00		.48		5	6						
112.9	115.0	09C12	2.1	2.1	4A13	3.08	.04	1.11	1.89	24.00		.69		8	9						
115.0	117.1	09C13	2.1	1.9	4A13	2.99	.03	.73	1.04	19.00		.55		6	7						
117.1	119.2	09C14	2.1	2.1	4A13	3.18	.05	1.17	2.50	27.00		.69		10	11						
119.2	121.3	09C15	2.1	2.1	4A13	3.23	.05	1.48	4.00	33.00		.82		11	12						



DDH: FAGA140

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														S.G. W.R.	
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAG %	HG %	MN %	AS %	BA %		
85.3	87.3	14544	2.0	1.5	4A4	3.60	.01	6.49	18.60	112.99		.89	2	7	9							
87.3	89.3	14545	2.0	1.5	4A43	3.54	.01	3.08	8.69	52.00		.40	2	14	16							

DDH: FAGA141

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAG %	HG %	MN %	AS %	BA %	S.G. W.R.
43.3	45.3	09266	2.0	.5	4A0	2.77	.03	1.03	.55	23.00			.27	1	1						
45.3	47.3	09267	2.0	1.8	4A4	3.01	.06	1.64	3.60	31.00			.69	8	8						
47.3	49.3	09268	2.0	1.7	4A0	2.84	.04	1.33	3.20	25.00			.48	2	3						
49.3	51.3	09269	2.0	2.0	4A0	3.01	.06	1.38	3.20	29.00			.55	9	10						
51.3	53.3	09270	2.0	2.0	4A0	3.02	.05	1.35	3.20	29.00	26.00		.62	5	5						
53.3	55.5	09271	2.2	2.2	4A0	2.93	.04	1.42	3.10	27.00			.48	5	5						
55.8	57.1	09272	1.3	1.3	4B4	3.01	.02	1.38	5.00	30.00			.34	3	5	9					
57.1	57.6	09273	.5	.4	4E4	4.05	.35	5.60	12.60	154.00			2.54	2	20	22					
58.6	60.8	09274	2.2	2.2	4C0	3.33	.04	1.00	3.00	27.00			.21	6	7	14					
65.6	66.6	09275	1.0	1.0	4L24	3.17	.02	.55	.84	17.00			.27	4	8	12					
68.5	69.7	09276	1.2	1.2	4E4	4.40	.18	12.30	18.70	166.00			2.26	1	21	22					
69.7	70.4	09277	.7	.7	4A14	3.34	.06	5.80	9.10	88.00			1.10	2	11	13					
70.4	71.0	09278	.6	.6	4D0	3.12	.06	3.50	5.10	53.00			.82	2	8	11					
71.0	73.0	09279	2.0	2.0	4A4	2.92	.03	1.85	4.50	42.00			.55	1	3	4					
73.0	75.0	09280	2.0	2.0	4A4	3.07	.02	1.83	4.60	40.00	39.00		.69	1	3	5					
75.0	76.7	09281	1.7	1.7	4A0	2.93	.02	1.25	1.62	20.00			.48	2	3	5					
77.6	79.6	09282	2.0	1.9	4A4	3.39	.05	4.70	8.30	66.00			1.10	1	12	14					
79.6	80.2	09283	.6	.6	4E4	3.90	.04	10.40	17.10	170.00			2.33	2	22	24					
80.5	81.4	09284	.9	.9	4E4	4.38	.05	8.40	14.80	146.00			1.65	2	23	25					
81.4	81.8	09285	.4	.4	4A4	3.68	.08	6.40	9.90	97.00			1.30	1	17	19					
82.4	83.4	09286	1.0	1.0	4A4	3.56	.04	5.30	9.40	90.00			1.10	1	15	17					
83.5	84.2	09287	.7	.7	4A4	3.34	.05	3.40	4.80	59.00			1.37	1	13	15					
84.4	84.8	09288	.4	.4	4A4	3.43	.06	3.50	3.00	61.00			1.44	1	15	17					
84.8	85.7	09289	.9	.9	4E4	4.83	.07	9.60	13.80	178.00	194.00		.48	1	24	26					
85.7	86.9	09290	1.2	.5	4A4	3.44	.03	5.40	8.50	100.00			1.65	1	11	12					
86.9	87.3	09291	.4	.4	4E4	4.63	.05	8.00	10.80	161.00			1.44	2	27	29					
87.3	88.3	09292	1.0	1.0	4A4	3.64	.15	6.30	8.80	100.00			1.03	2	12	14					
88.5	88.9	09293	.4	.4	4D4	3.60	.11	5.10	8.10	87.00			1.23	4	12	16					
89.1	89.8	09294	.7	.7	4A4	3.42	.04	3.40	7.40	58.00			1.03	2	12	14					
77.0	77.6	09295	.6	.6	4C0	3.45	.04	.59	3.10	18.00			.75	3	17	20					

DDH: FAGA142

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PC %	PY %	TOT FE	BAC %	HG %	MN %	AS %	BA %
50.5	51.6	05301	1.1	.0	4CG	3.93	.13	5.98	5.79	72.00		.48	4	14	19					
51.6	53.6	05302	2.0	.0	4EK	4.57	.07	3.76	2.17	51.00		1.03	1	32	34					
53.6	55.8	05303	2.2	.0	4EO	4.44	.15	2.77	2.24	43.00		1.17	2	32	34					
55.8	57.4	05304	1.6	.0	4KE	4.46	.17	5.46	2.51	68.00		1.65	5	27	33					
57.4	58.7	05305	1.3	.0	4EG	4.57	.16	6.90	7.35	85.00	83.00	.82	2	21	23					
58.7	60.6	05306	1.9	.0	4EO	4.76	.08	3.01	2.71	49.00		.41	1	34	35					
89.9	90.7	05307	.8	.0	4A4	3.22	.09	2.21	4.82	38.00		1.58	1	9	11					
90.7	92.7	05308	2.0	.0	4E4	4.57	.26	2.84	4.12	47.00		.62	3	30	34					
92.7	93.7	05309	1.0	.0	4E4	4.62	.50	5.71	12.27	99.00		.75	4	24	29					
93.7	95.1	05310	1.4	.0	4E4	4.67	.15	6.45	12.75	95.00		.62	3	25	29					
95.1	98.6	05311	3.5	.0	4AO	2.79	.02	.41	1.65	6.00		.75	3	4	8					
98.6	100.6	05312	2.0	.0	4E4	4.81	.21	5.15	7.55	106.00		.69	2	29	32					
100.6	102.1	05313	1.5	.0	4E4	4.79	.24	4.52	8.47	93.00		.82	2	30	32					
102.1	103.3	05314	1.2	.0	4E4	4.37	.13	3.95	9.08	70.00		.55	4	26	31					
154.9	156.4	05315	1.5	.0	4D4	3.80	.25	6.34	4.25	128.00	131.00	.48	3	19	22					
156.4	157.2	05316	.8	.0	4D0	3.86	.28	2.46	3.27	41.00		.27	2	25	27					
157.2	159.2	05317	2.0	.0	4A4	3.50	.10	4.71	8.04	69.00		.69	2	15	18					
159.2	161.5	05318	2.3	.0	4A4	3.56	.11	4.35	7.28	61.00		1.03	2	17	20					
161.5	163.5	05319	2.0	.0	4CA	3.36	.21	.42	3.98	12.00		.96	4	15	20					
163.5	165.0	05320	1.5	.0	4CA	3.21	.79	.45	2.73	22.00		.27	5	19	24					
165.0	166.1	05321	1.1	.0	4CA	3.83	.52	4.17	3.81	69.00		1.37	5	22	27					
198.7	200.4	05322	1.7	.0	4EL	3.65	.26	2.06	2.56	25.00		1.65								
242.8	243.5	05323	.7	.0	4E8	4.26	.18	3.60	3.67	56.00		.89	8	24	33					
243.5	244.3	05324	.8	.0	4L0	2.93	.19	.78	.60	12.00		.34	4	3	8					
244.3	245.1	05325	.8	.0	4E8	4.35	.26	5.23	4.32	69.00		.55	12	21	33					
245.1	245.7	05326	.6	.0	4D0	3.32	.15	3.40	3.11	39.00	39.00	1.23	4	16	20					
245.7	247.7	05327	2.0	.0	4E8	3.99	.19	4.38	3.47	56.00		2.06	10	21	32					
247.7	249.2	05328	1.5	.0	4E8	3.78	.18	3.98	3.68	49.00		1.51	9	17	27					
249.2	250.2	05329	1.0	.0	4E8	3.84	.21	4.80	4.29	59.00		.07	10	17	28					
250.2	252.4	05330	2.2	.0	4EL	3.74	.17	2.70	2.57	40.00		.89	10	20	30					
252.4	253.0	05331	.6	.0	4KL	3.97	.08	4.76	3.83	82.00		1.03	10	22	32					

DDH: FAGA143

-----DEPTHS-----				-----ASSAYS-----																	
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAC %	HG %	MN %	AS %	BA %	S.G. W.R.	
140.5	141.8	01644	1.3	.8	4L0	3.27	.03	3.78	7.10	59.00	.55	2	10	12							
145.1	146.9	01645	1.8	1.8	4E0	4.30	.04	4.09	5.73	87.00	.62	1	27	29							
146.9	148.3	01646	1.4	1.4	4D0	3.22	.11	1.87	3.29	30.00	.75	2	13	15							

DDH: FAGA145

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													S.G. W.R.	
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAD %	HG %	MN %	AS %		BA %
41.8	43.3	05199	1.5	1.5	4L0	3.11	.09	.81	.94	13.00		.41									
48.0	50.3	05200	2.3	1.9	4K4	4.52	.12	11.40	12.80	148.00		.89	3	21	25						
78.3	80.0	05214	1.7	1.5	4C0	3.57	.14	1.39	2.85	26.00	35.00	.96	2	19	21						
80.0	83.1	05215	3.1	2.4	4K4	4.59	.29	3.28	3.59	55.00		1.17	2	33	36						







DDH: FAGA152

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													S.G. W.R.
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAO %	HG %	MN %	AS %	
93.3	94.8	05359	1.5	1.4	4A3	2.85	.05	.13	.37	5.00			2.19							
94.8	96.3	05360	1.5	1.3	4A3	2.81	.06	.17	.22	7.00			.21							
96.3	97.8	05361	1.5	1.5	4A3	2.81	.05	.12	.15	6.00			.34							
97.8	99.3	05362	1.5	1.4	4A3	2.99	.15	.07	.18	7.00			.48							
99.3	100.8	05363	1.5	1.5	4A3	3.08	.14	.10	.34	7.00			.21							
100.8	101.8	05364	1.0	1.0	4A3	2.90	.15	.05	.10	6.00			.21							
104.3	106.3	05365	2.0	1.4	4A3	2.98	.16	.07	.21	5.00			.41							
106.3	108.3	05366	2.0	.0	4A3	2.87							.48							
108.3	110.3	05367	2.0	2.0	4A3	2.87	.07	.01	.15	3.00			.27							
110.3	112.3	05368	2.0	2.0	4A3	2.82	.11	.01	.18	3.00			.27							
112.3	114.3	05369	2.0	1.7	4A3	3.06	.13	.03	.55	5.00			.27							
114.3	116.3	05370	2.0	1.6	4A3	2.90	.13	.02	.36	5.00			.21							
116.3	118.3	05371	2.0	2.0	4A3	2.93	.07	.02	.38	3.00			.21							
118.3	120.3	05372	2.0	2.0	4A3	2.89	.07	.01	.20	2.00			.21							
120.3	122.3	05373	2.0	2.0	4A3	2.82	.16	.01	.51	5.00			.34							
122.3	124.3	05374	2.0	1.9	4A3	2.85	.23	.01	.38	6.00			.34							
124.3	126.3	05375	2.0	1.9	4A3	2.88	.18	.01	.68	5.00			.41							
126.3	128.3	05376	2.0	2.0	4A3	2.91	.17	.01	.32	3.00			.21							
128.3	130.3	05377	2.0	1.0	4A3	2.82	.16	.02	.19	4.00			.27							
130.3	132.0	05378	1.7	1.7	4A3	2.88	.10	.01	.25	4.00			3.02							
136.2	138.2	05379	2.0	2.0	4A3	2.83	.15	.01	.19	4.00			.27							
138.2	140.2	05380	2.0	1.8	4A3	2.90	.25	.01	.21	4.00			.34							
140.2	142.2	05381	2.0	2.0	4A3	2.75	.15	.01	.09	2.00			.21							
142.2	144.2	05382	2.0	1.7	4A3	2.80	.13	.01	.04	3.00			.21							
144.5	146.7	05383	2.2	2.0	4A3	2.96	.12	.48	.77	10.00			.62	1	10	11				
146.7	148.4	05384	1.7	1.5	4D4	3.89	.23	1.70	3.32	29.00			1.23	1	27	29				
148.4	150.9	05385	2.5	2.3	4A4	2.88	.10	1.72	2.95	26.00			.48	1	6	8				
175.3	177.3	05386	2.0	1.9	4L1	3.08	.11	1.18	.91	12.00			.27	9	4	13				
177.3	179.0	05387	1.7	1.4	4L1	3.09	.08	2.45	1.88	23.00			.14	8	2	11				
179.0	180.3	05388	1.3	1.1	4L7	3.29	.15	2.26	3.10	25.00			.55	5	13	18				
185.3	186.8	05389	1.5	1.5	4A3	2.72	.03	.58	.88	9.00			.14							
186.8	188.1	05390	1.3	1.0	4A3	2.77	.06	.64	.94	11.00			.21							
200.6	202.6	05391	2.0	1.6	4E8	3.98	.37	1.53	1.35	23.00			1.23	4	27	31				
202.6	204.6	05392	2.0	2.0	4C8	3.80	.36	.78	.95	18.00			.69	3	26	29				
204.6	206.0	05393	1.4	1.3	4G4	3.76	.13	4.78	5.55	69.00			1.30	4	13	17				





DDH: FAGA155

						-----ASSAYS-----															
DEPTHS	SAMPLE	INT.	REC.	ROCK	S.G.	CU	PB	ZN	AG(AA)	AG(FA)	AU(FA)	PO	PY	TOT	BAC	HG	MN	AS	BA	S.G.	
FROM	TO	NO.		UNIT	PULP	%	%	%	G/MT	G/MT	G/MT	%	%	FE	%	%	%	%	%	W.R.	
41.8	43.6	07474	1.8	1.6	4A41	3.14	.08	1.95	3.89	41.00				.62	9	10					
43.6	44.9	07475	1.3	1.3	4A41	3.08	.02	2.83	5.59	47.00				.75	1	5	6				
44.9	45.6	07476	.7	.6	4D4	3.20	.05	3.99	9.59	71.00				.55	3	5	8				
45.6	47.7	07477	2.1	2.1	4A43	3.25	.05	2.81	5.79	48.00				.75	9	10					
47.7	49.4	07478	1.7	1.7	4A43	3.22	.04	3.49	6.20	55.99				1.10	1	8	9				
49.4	51.5	07479	2.1	2.1	4A43	3.14	.04	2.64	5.29	43.00				1.37	1	6	7				
51.5	52.9	07480	1.4	1.4	4A43	3.10	.02	2.50	6.09	44.00				.89	6	7					
52.9	53.3	07481	.4	.4	4E4	4.08	.02	10.09	1.97	168.00	170.00			2.06	3	14	17				
53.3	54.1	07482	.8	.8	4A31	3.33	.04	3.70	7.40	60.99				.89	1	9	11				
56.9	57.7	07483	.8	.7	4D0	3.54	.11	2.79	6.79	55.99				.81	4	13	17				
57.7	59.1	07484	1.4	1.4	4D4	3.06	.05	4.79	6.20	79.00				.75	2	2	5				
59.1	60.7	07485	1.6	1.5	4D4	3.04	.04	3.60	6.59	61.99				.89	2	2	4				
60.7	62.3	07486	1.6	1.6	4D0	3.00	.04	2.39	3.70	41.00				.62	3	2	6				
62.3	63.1	07487	.8	.8	4A10	3.04	.04	1.99	2.70	35.00				.89	6	7					
63.1	64.0	07488	.9	.9	4A14	3.27	.05	2.50	3.79	45.00				1.03	11	11					
64.0	66.0	07489	2.0	2.0	4A10	3.04	.04	1.19	1.24	22.00				.68	7	7					
66.0	67.8	07490	1.8	1.8	4A30	3.33	.05	.86	1.55	22.00				1.10	1	20	22				
67.8	69.5	07491	1.7	1.7	4A0	3.06	.05	.81	1.82	24.00	20.00			.55	11	12					
69.5	71.2	07492	1.7	1.7	4A4	3.02	.04	3.39	4.50	56.99				.89	1	5	6				
74.9	75.9	07493	1.0	1.0	4A0		.04	.47	.63	14.99											
75.9	76.6	07494	.7	.6	5D4*		.02	.07	.44	.99											
76.6	77.4	07495	.8	.8	4D0	3.27	.05	3.81	2.06	41.00				2.12	1	10	12				
77.4	79.6	07496	2.2	2.2	4E41	3.02	.08	7.20	12.59	115.99				1.70	1	15	17				
79.6	80.5	07497	.9	.9	4A4	3.41	.05	5.50	6.90	84.00				1.70	2	10	12				
80.5	81.7	07498	1.2	1.2	4E4	3.91	.05	10.69	17.19	182.00				2.54	2	12	15				
81.7	83.9	07499	2.2	2.2	3G0	2.98	.01	.49	.64	11.00				.27	3	3	6				
83.9	84.9	07500	1.0	1.0	4A1	3.93	.02	1.86	3.99	43.00				2.74	2	9	11				
84.9	85.6	07501	.7	.7	5D4a	2.99	.02	.16	1.86	1.99				.47	7	1	9				
85.6	87.2	07502	1.6	1.6	4A4	3.25	.02	2.75	6.29	53.00				.68	4	7	12				

DDH: FAGA156

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														S.G. W.R.
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAO %	HG %	MN %	AS %	BA %	
85.1	87.1	14654	2.0	1.7	4A41	3.35	.04	2.98	5.00	46.00		1.03	2	12	14						
87.1	88.7	14655	1.6	1.6	4A41	3.20	.10	1.91	3.14	31.99		.89	5	8	13						
88.7	89.7	14656	1.0	.9	4D0	3.20	.05	1.74	3.83	29.99		.75	5	10	15						
91.3	92.4	14657	1.1	1.0	4C0	2.98	.01	1.37	2.56	18.00		.47	2	4	6						
95.9	97.4	14658	1.5	1.5	4 ACD	3.10	.05	1.68	2.95	28.99		.40	2	2	5						
97.4	98.9	14659	1.5	1.5	4C0	2.91	.02	1.27	2.89	24.00		.62	1	1	3						
98.9	100.9	14660	2.0	1.4	4A1	3.00	.02	1.38	2.27	24.00		.55	2	2	4						
100.9	103.4	14661	2.5	1.9	4A14	3.16	.02	3.74	5.09	60.99		.40	1	4	5						
103.4	104.2	14662	.8	.8	4D514	3.72	.04	3.45	7.20	67.00		.68	5	14	20						
106.2	109.0	14663	2.8	2.5	4A14	3.10	.04	1.87	4.29	30.99		.62	1	6	7						
109.0	109.7	14664	.7	.7	4ACD	3.10	.02	1.40	2.91	28.99		.47	3	2	6						
109.7	111.5	14665	1.8	1.5	4A14	3.25	.10	4.16	5.90	60.99		.89	1	7	9						
111.5	113.2	14666	1.7	1.7	4A14	3.64	.08	3.64	4.32	55.00		.55	2	8	10						
113.2	114.3	14667	1.1	1.1	4A14	3.12	.05	2.97	4.34	51.00		.89	2	4	7						
114.3	116.3	14668	2.0	2.0	4D54	3.10	.05	4.01	6.40	65.00		1.30	1	2	3						
116.3	118.3	14669	2.0	2.0	4D5	3.02	.02	3.33	5.70	53.00		.55	1	1	3						
118.3	119.5	14670	1.2	1.2	4D5	3.02	.02	2.24	3.83	31.99		.47	1	2	4						
122.3	124.0	14671	1.7	1.3	4D5	2.95	.02	2.22	3.29	30.99		.34	1	1	3						
124.0	126.3	14672	2.3	2.2	4A14	3.25	.04	2.29	6.29	39.00		.40	1	5	7						
126.3	128.3	14673	2.0	1.1	4D0	3.06	.02	2.25	5.29	37.00		.27	2	2	5						
128.3	130.6	14674	2.3	1.3	4D0	3.08	.01	2.37	6.20	42.00		.01	2	2	5						
132.7	134.2	14675	1.5	1.4	4D5	3.10	.05	2.00	3.04	33.00		.40	4	5	9						
134.2	135.3	14676	1.1	1.0	5D*	3.04	.02	2.73	1.83	41.00		2.54	5	1	6						
135.3	136.7	14677	1.4	1.4	4D0	3.12	.02	3.31	5.20	51.00		.47	3	2	6						
136.7	138.7	14678	2.0	2.0	4A14	3.12	.04	2.70	3.91	39.00		.81	1	4	6						
138.7	140.7	14679	2.0	1.8	4A14	3.14	.04	2.68	4.59	50.00		.75	1	6	7						
140.7	142.7	14680	2.0	1.9	4A10	3.06	.02	1.57	3.39	30.99		.47		5	5						
142.7	144.7	14681	2.0	2.0	4A10	3.06	.04	1.29	2.20	27.99		.47		7	8						
144.7	146.7	14682	2.0	2.0	4A10	3.06	.02	1.37	3.00	27.00		.40	1	6	7						
146.7	148.7	14683	2.0	1.3	4A10	3.10	.02	1.46	1.42	27.00		.55		8	9						
148.7	150.7	14684	2.0	1.8	4A10	3.22	.02	2.12	2.58	30.99		.68	1	7	8						
150.7	154.7	14685	4.0	3.2	4A10	3.20	.04	1.20	1.57	24.00		.47	1	7	8						
154.7	156.7	14687	2.0	1.9	4A14	3.29	.05	2.08	5.20	36.00		.47	1	10	11						
156.7	157.9	14688	1.2	1.2	4A10	3.00	.05	1.24	2.56	25.00		.34	1	10	11						
169.8	170.7	14689	.9	.8	4C4	3.10	.02	3.33	11.19	77.00		.20	1	4	6						
174.3	175.5	14690	1.2	1.2	4A4	3.89	.04	3.43	8.90	72.00		1.10	2	1	3						
175.5	177.0	14691	1.5	1.5	4A10	3.06	.02	1.80	2.97	28.99		.47	2	19	22						
194.3	196.3	14692	2.0	1.8	4C5	3.25	.04	1.86	2.93	30.99		.75	3	4	7						
196.3	198.3	14693	2.0	1.8	4DA	3.24	.02	3.45	4.57	60.99		.95	1	10	12						
198.3	200.3	14694	2.0	1.9	4DA	3.24	.02	2.70	5.29	49.00		.75	1	9	11						
200.3	201.5	14695	1.2	1.2	4A14	3.16	.05	1.87	3.14	30.99		1.70	1	9	11						
201.5	202.3	14696	.8	.7	4A0	3.02	.02	1.69	3.16	24.00		.47	2	7	10						



DDH: FAGA158

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														S.G. W.R.
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAC %	HG %	MN %	AS %	BA %	
17.7	20.1	11921	2.4	1.4	4E4	4.28	.05	6.90	10.80	129.00		1.03	2	24	27						
20.1	23.2	11922	3.1	1.2	4D4	3.08	.02	3.00	5.79	54.00		.62	2	5	8						
49.4	51.6	11923	2.2	2.0	4D0	3.02	.01	2.20	5.50	49.00		.75	3	4	7						
51.6	53.5	11924	1.9	1.9	4D0	3.12	.02	2.60	6.50	53.00		.95	3	5	9						
67.5	68.5	11925	1.0	1.0	4D0	3.04	.01	2.50	6.90	51.00		.75	3	3	6						
69.0	71.0	11926	2.0	2.0	4DE	3.16	.02	1.97	6.00	40.00		.81	5	5	11						
91.2	94.1	11927	2.9	2.8	4AD	2.98	.02	2.10	4.79	39.00		.95	1	4	6						
96.5	99.0	11928	2.5	2.5	4A0	2.95	.01	.13	.33	3.99		.68	4	1	6						
99.0	101.8	11929	2.8	2.8	4A4	3.00	.02	2.20	4.50	43.00		.27	1	3	5						
103.2	105.1	11930	1.9	1.1	4E1	3.64	.02	1.29	4.29	27.99	22.00	.47	5	18	23						
105.1	106.6	11931	1.5	1.4	4A43	3.64	.02	1.03	4.40	28.99		.47	7	16	24						
110.8	113.0	11932	2.2	2.0	4H1	3.76	.17	4.59	6.00	92.00		.34	15	11	27						
113.0	114.7	11933	1.7	1.6	4AE	3.89	.22	7.49	12.19	158.00		.55	2	17	20						
115.8	117.2	11934	1.4	1.4	4A4	3.25	.02	2.20	3.70	42.00		.68	1	8	10						
118.3	119.8	11935	1.5	1.5	4A4	3.33	.04	3.29	5.40	52.00		1.03	2	9	12						
119.8	121.0	11936	1.2	1.2	4L0	3.56	.11	3.10	4.79	55.00		1.51	3	16	20						
121.0	123.3	11937	2.3	1.4	4AD	3.68	.08	4.29	8.40	83.00		1.43	5	14	20						
125.7	128.7	11938	3.0	2.4	4A4	3.41	.04	4.90	9.50	96.00		1.43	2	10	12						
128.7	131.6	11939	2.9	2.9	4A4	3.08	.02	1.88	4.40	28.99		.68	4	4	9						

DDH: FAGA150

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													S.G. W.R.		
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PC %	PY %	TOT FE	BAC %	HG %	MN %	AS %		BA %	
102.7	103.5	11268	.8	.8	4E*4	4.67	.19	4.30	1.88	58.00	53.00	2.88	3	35	38							
103.5	104.5	11269	1.0	1.0	4A3	3.74	.17	.68	.98	23.00		1.30	2	21	23							
104.5	105.2	11270	.7	.7	4E*4	4.23	.19	4.00	4.80	67.00		1.17	3	24	27							
107.0	107.5	11271	.5	.4	4A1	3.33	.08	.80	.79	18.00		.21	5	11	16							
107.5	107.8	11272	.3	.3	4E*4	4.24	.19	3.30	4.00	54.00		1.03	3	27	30							
107.8	108.5	11273	.7	.6	4E*4	3.92	.15	2.40	2.10	37.00		1.17	2	23	26							
108.5	109.2	11274	.7	.7	4C*	3.67	.11	2.20	1.92	28.00		.69	4	15	20							
109.2	111.4	11275	2.2	2.2	4E*4	4.83	.29	2.30	1.92	37.00		1.23	3	32	35							
111.4	111.8	11276	.4	.4	4E*4	4.81	.19	5.70	7.40	104.00		1.51	1	31	32							
111.8	112.3	11277	.5	.5	4C0	3.45	.14	1.32	1.43	30.00		.34	7	10	17							

DDH: FAGA160

---DEPTHS---			SAMPLE INT. NO.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													S.G. W.R.
FROM	TO	CU %					PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAG %	HG %	MN %	AS %	BA %	
49.2	51.5	08332	2.3	2.2	4A0	2.99	.01	1.38	3.10	28.99		.47	5	6						
51.5	54.0	08333	2.5	1.5	4A0	2.95	.01	1.56	5.00	39.00		.55	5	5						
54.0	56.1	08334	2.1	1.0	4AG	3.10	.01	2.06	5.70	47.00		.75	1	8	9					
65.9	68.0	08335	2.1	2.0	4A0	3.14	.02	2.50	5.70	43.00		.75	3	8	11					
68.0	70.2	08336	2.2	2.2	4DA4	3.16	.04	2.79	4.79	50.00		.89	2	8	10					
71.3	73.5	08337	2.2	2.1	4A4	3.18	.02	4.09	9.40	80.00	73.00	.75	1	12	14					
73.5	75.7	08338	2.2	2.2	4A4	3.10	.04	3.89	5.40	65.00		.75	2	7	9					
79.2	81.1	08339	1.9	1.8	4C0		.07	.93	1.22	19.00										
84.3	86.0	08340	1.7	1.6	4C0	2.89	.04	1.08	1.70	20.00		.47	2	2	4					
86.0	87.8	08341	1.8	1.6	4C0	2.95	.05	.98	1.11	19.00		.68	2	3	6					
88.6	90.3	08342	1.7	1.7	4B0	2.89	.04	.72	.88	18.00		.27	2	2	5					
95.6	97.5	08343	1.9	1.9	4A4	2.99	.02	1.69	5.09	27.99		.27	3	1	5					
97.5	99.5	08344	2.0	1.0	4A0	2.87	.02	1.01	2.29	17.00		.27	3	1	4					
99.5	101.5	08345	2.0	1.2	4A4	2.93	.02	1.81	3.99	29.99		.34	1	3	5					
101.5	102.1	08346	.6	.6	4ED	3.66	.05	1.96	5.20	34.00		.47	2	22	24					
108.6	110.0	08347	1.4	.0	4A0	2.99	.02	1.37	3.20	27.00		.55	5	5						
110.0	112.0	08348	2.0	2.0	4A0	2.95	.05	1.84	2.89	35.00	35.00	1.03	13	14						
112.0	113.7	08349	1.7	1.6	4A0	3.14	.05	.46	1.02	12.00		.47	11	11						
116.8	118.3	08350	1.5	1.5	4L4		.04	.59	.48	10.00										
118.3	119.8	08351	1.5	1.1	4L4		.08	.51	.77	12.00										
120.6	121.8	08352	1.2	1.2	4D0	3.02	.02	1.85	3.79	25.00		.20	2	2	4					
121.8	123.4	08353	1.6	1.6	4H14	3.54	.08	2.89	6.50	57.99		.40	13	8	22					
123.4	125.2	08354	1.8	1.8	4D0	2.52	.10	3.29	5.00	59.99		1.03	2	9	12					
125.2	126.9	08355	1.7	1.7	4D0	3.10	.05	3.20	5.70	55.00		.55	3	5	8					
129.4	130.8	08356	1.4	1.4	4D0	3.04	.02	1.97	4.59	33.00		.47	3	3	6					
130.8	132.0	08357	1.2	1.0	4A4	2.87	.02	1.50	3.89	23.00		.27	1		2					
132.0	134.1	08358	2.1	1.6	4D0	3.52	.07	3.20	5.59	46.00		.40	5	9	15					



DDH: FAGA162

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														S.G. W.R.
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAO %	HG %	MN %	AS %	BA %	
62.3	63.2	06664	.9	.9	4EL1	3.81	.27	1.09	1.10	20.00		.21	10	13	24						
63.2	65.0	06665	1.8	1.6	4KL8	3.86	.16	2.60	2.60	33.00		.69	6	21	28						
65.0	66.4	06666	1.4	1.4	4E0	4.84	.10	3.40	1.60	45.00	43.00	1.51	4	32	37						
66.4	67.5	06667	1.1	1.0	4CL5		.24	.27	.49	19.00											
67.5	69.2	06668	1.7	1.7	4CA3		.11	.16	.25	8.00											
69.2	70.9	06669	1.7	1.7	4CA3		.10	.08	.21	9.00											
70.9	72.0	06670	1.1	1.1	4CE0		.30	.10	.22	20.00											
72.0	74.5	06671	2.5	2.4	4CA3		.19	.11	.21	14.00											
74.5	76.9	06672	2.4	2.2	4CA3		.13	.14	.29	11.00											
76.9	78.0	06673	1.1	1.1	4CL5		.13	.18	.26	11.00											
78.0	80.5	06674	2.5	2.2	4E*	4.42	.12	2.09	1.08	51.00		.96	5	31	36						
80.5	82.0	06675	1.5	1.5	4AC3	3.35	.17	.17	.26	12.00		.69	2	18	20						
82.0	83.5	06676	1.5	1.5	4CL*	3.70	.21	.47	1.69	18.00		.55	4	18	23						
83.5	84.8	06677	1.3	1.2	4GE4	4.56	.21	6.50	7.80	100.00		1.44	3	25	28						



















DDH: FAGA204

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													S.G. W.R.
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAO %	HG %	MN %	AS %	
100.5	102.0	05580	1.5	1.5	4L2	2.94	.06	.69	.68	13.00		.27								
102.0	103.5	05581	1.5	1.5	4L2	2.85	.04	.42	.61	5.00		.14								
103.5	105.0	05582	1.5	1.5	4L2	2.85	.04	1.06	.32	10.00		.55								
105.0	106.6	05583	1.6	1.6	4L2	2.83	.03	.55	.26	6.00		.75								
106.6	108.2	05584	1.6	1.1	4L2	2.88	.03	1.12	.51	13.00		.27								
108.2	109.7	05585	1.5	1.4	4A3	2.85	.04	.03	.05	2.00		.21								
109.7	111.3	05586	1.6	1.5	4A3	2.82	.03	.04	.13	1.00		.14								
111.3	112.1	05587	.8	.8	4C0	3.01	.07	.04	.17	4.00		.34								
112.1	113.6	05588	1.5	1.5	4L2	2.88	.04	.06	.13	15.00		.21								
113.6	115.1	05589	1.5	1.5	4L2	2.83	.02	.17	.10	4.00		.14								
115.1	116.7	05590	1.6	1.6	4L2	2.91	.02	.43	.09	6.00		.41								
116.7	118.3	05591	1.6	1.5	4L2	2.84	.01	.27	.15	4.00		.07								
135.6	136.9	05592	1.3	1.3	4A3	2.98	.17	.13	.37	5.00		.75								
136.9	138.2	05593	1.3	1.1	4A3	3.08	.15	.12	.56	5.00		.34								
138.2	139.5	05594	1.3	.8	4A3	2.93	.10	.18	.35	6.00		.34								
139.5	140.9	05595	1.4	1.1	4A3	2.87	.07	.02	.32	2.00		.14								
140.9	142.3	05596	1.4	1.4	4A3	3.02	.13	.02	.14	4.00		.48								
142.9	144.4	05597	1.5	1.4	4A3	2.90	.04	.14	.26	4.00		.14								
144.4	145.9	05598	1.5	1.5	4A3	2.92	.09	.10	.30	5.00		.21								
145.9	147.3	05599	1.4	1.4	4A3	2.96	.11	.50	1.07	14.00		.41								
147.3	148.7	05600	1.4	1.4	4A3	2.91	.02	1.55	3.00	35.00		.41								
148.7	150.1	05601	1.4	1.2	4A3	2.93	.01	.69	1.53	14.00		.34								
166.8	168.4	05602	1.6	1.6	4L2	2.97	.05	1.23	1.05	15.00		.21								
168.4	170.1	05603	1.7	1.7	4L2	2.83	.06	.43	.22	9.00		.14								
171.7	172.6	05604	.9	.9	4G4	4.55	.02	4.30	6.50	59.00		.41								
178.0	179.2	05605	1.2	1.2	4A3	3.21	.02	2.60	4.40	43.00		.55	1	12	14					
179.2	180.6	05606	1.4	1.4	4G4	4.54	.16	5.80	8.70	98.00		1.58		17	17					
180.6	181.9	05607	1.3	1.3	4G4	4.63	.07	5.10	8.50	76.00		.82	1	15	16					
181.9	183.2	05608	1.3	1.2	4E0	4.50	.21	2.70	2.40	33.00		1.10	3	33	37					
183.2	184.5	05609	1.3	1.2	4E0	4.33	.32	1.39	1.40	23.00		4.25	3	31	34					
184.5	186.2	05610	1.7	1.1	4G4	4.27	.16	7.20	11.00	117.00		.41	1	20	21					
186.2	187.5	05611	1.3	1.3	4E0	4.29	.27	2.11	2.60	35.00	35.00	3.09	2	30	33					
187.5	188.8	05612	1.3	1.2	4E0	4.23	.26	.92	.56	20.00		1.03	4	31	35					
188.8	190.0	05613	1.2	1.2	4C8	4.41	.34	1.24	1.59	22.00		1.37	8	26	34					
190.0	191.2	05614	1.2	1.2	4C8	4.29	.20	.59	.23	12.00		1.17	3	30	34					
191.2	192.3	05615	1.1	.9	4C8	3.71	.25	3.40	3.80	53.00		1.30	3	20	23					





DDH: FAGA206

-----DEPTHS-----			SAMPLE INT. NO.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAO %	HG %	MN %	AS %	BA %
104.5	108.8	05680	4.3	1.3	4EG	4.01	.22	5.80	11.00	104.00		.82	2	19	21					
126.8	129.8	05682	3.0	.8	4A0	2.67	.06	.14	.17	5.00		.82								
129.8	132.6	05683	2.8	1.0	4A0	2.76	.05	.23	.42	7.00		.41								
132.6	133.1	05684	.5	.5	4C0	3.22	.13	.18	.70	5.00		.14								
201.9	203.6	05685	1.7	1.5	4A3	2.90	.16	.18	.20	5.00		.41								
224.5	227.1	05686	2.6	1.4	4C8	3.55	.14	2.70	2.90	39.00		.48	12	15	28					
227.1	228.6	05687	1.5	1.3	4C8	3.89	.14	4.00	3.50	41.00	36.00	1.30	7	20	28					
228.6	229.7	05688	1.1	1.1	4C8	3.91	.24	2.01	.99	30.00		1.44	10	25	35					
229.7	231.1	05689	1.4	1.4	4C8	3.91	.11	2.90	1.13	44.00		1.51	10	24	34					
231.1	232.5	05690	1.4	1.4	4C8	3.98	.21	.98	.62	24.00		2.19	8	27	36					
254.6	255.8	05691	1.2	1.2	4A3	3.27	.14	1.46	1.45	26.00		.55								
255.8	256.8	05692	1.0	1.0	4A3	2.86	.19	.56	.70	12.00		.96								
256.8	257.9	05693	1.1	1.1	4A3	2.99	.18	1.33	1.68	23.00		.55								
236.3	237.8	05828	1.5	1.5	4L2	3.05	.14	.12	.25	5.00		.27								
237.8	239.3	05829	1.5	1.5	4L2	3.06	.43	.07	.12	5.00		.14								
239.3	240.8	05830	1.5	1.4	4L2	3.09	.18	.03	.03	3.00		.14								
240.8	242.3	05831	1.5	.5	4L2	2.99	.11	.04	.03	2.00		.07								
242.3	243.9	05832	1.6	1.6	4L2	2.88	.02	.02	.03	1.00		.07								
243.9	245.5	05833	1.6	.8	4L2	2.93	.04	.01	.04	2.00		.07								
245.5	247.1	05834	1.6	1.6	4L2	2.93	.08	.01	.06	1.00		.34								
248.4	249.6	05835	1.2	1.2	4L2	2.90	.04	.01	.07	1.00		.07								
259.6	261.1	05836	1.5	1.5	4L2	2.93	.07	.09	.11	4.00		.07								
261.1	262.6	05837	1.5	1.5	4L2	2.91	.09	.14	.05	3.00		.07								
262.6	264.1	05838	1.5	1.5	4L2	2.93	.07	.14	.21	2.00		.07								
264.1	265.6	05839	1.5	1.5	4L2	2.99	.09	.24	.16	4.00		.14								
265.6	267.2	05840	1.6	1.6	4L2	2.93	.07	.05	.13	4.00		.07								
267.2	268.8	05841	1.6	1.6	4L2	2.96	.10	.13	.11	5.00		.14								
268.8	270.4	05842	1.6	1.6	4L2	2.93	.09	.07	.19	3.00		.07								
278.2	280.1	05843	1.9	1.5	4L2	2.97	.10	.08	.33	4.00		.07								



DDH: FAGA208

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAC %	HG %	MN %	AS %	BA %	S.G. W.R.
76.7	77.6	05801	.9	.9	4C0	3.82	.39	3.40	3.00	60.00		.27	7	21	28						
77.6	78.4	05802	.8	.8	4L2	2.84	.09	.14	.03	4.00		.14	1	3	5						
78.4	80.0	05803	1.6	1.6	4C0	3.57	.23	1.08	.74	22.00		.34	4	16	20						
80.0	81.6	05804	1.6	1.6	4C0	3.87	.20	2.40	1.72	39.00		.55	3	25	28						
81.6	82.7	05805	1.1	1.1	4L2	3.09	.06	.83	.43	13.00		.21	1	10	12						
82.7	83.5	05806	.8	.8	4D4	4.09	.18	6.70	8.30	109.00		.82	2	18	20						
83.5	84.2	05807	.7	.7	4D4	4.64	.22	5.80	8.70	99.00		6.58	3	32	35						
84.2	85.6	05808	1.4	1.4	4G4	4.45	.05	5.90	12.30	115.00		.75		16	17						
85.6	87.0	05809	1.4	1.4	4G4	4.47	.10	4.70	7.57	77.00		.41	1	10	12						
87.0	88.4	05810	1.4	1.4	4G4	4.50	.05	5.70	8.23	80.00		1.44		8	9						
125.5	126.4	05811	.9	.9	4E4	4.00	.24	3.40	4.50	55.00		1.99									
140.3	141.8	05812	1.5	1.5	4A3	3.00	.07	1.08	2.53	20.00		.34									
141.8	143.3	05813	1.5	1.3	4A3	2.92	.08	.51	.81	10.00		.34									
143.3	144.8	05814	1.5	1.5	4A3	2.83	.07	.68	1.23	12.00		.41									
144.8	146.3	05815	1.5	.9	4A3	2.87	.07	.95	1.95	16.00		.41									
146.3	147.7	05816	1.4	1.4	4A3	2.84	.07	.70	1.20	11.00		.41									
147.7	149.1	05817	1.4	1.4	4A3	2.82	.05	.63	1.25	11.00		.27	1	3	5						
149.1	150.5	05818	1.4	1.4	4A3	2.85	.07	.65	1.07	11.00		.21	1	4	6						
150.5	153.3	05819	2.8	1.8	4A3	2.86	.07	1.16	1.91	16.00	20.00	.34	1	3	5						
153.3	154.7	05820	1.4	1.4	4A3	2.77	.05	.31	.57	6.00		.27	1	3	4						
154.7	156.1	05821	1.4	1.4	4A3	2.86	.07	1.02	2.30	14.00		.48	1	3	5						
172.4	173.9	05823	1.5	1.5	4D0	3.49	.20	3.40	3.93	59.00		1.51	2	17	19						
173.9	175.3	05824	1.4	1.3	4C0	3.55	.25	.58	.35	14.00		1.44	1	19	21						
175.3	176.7	05825	1.4	1.4	4C0	3.52	.33	1.42	1.81	18.00		1.10	1	20	22						
176.7	178.1	05826	1.4	1.4	4C0	3.64	.27	.37	.84	18.00		1.51	1	24	25						

DDH: FAGA209

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													S.G. W.R.		
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAG %	HG %	MN %	AS %		BA %	
65.0	65.8	05915	.8	.8	4EG	4.84	.18	4.10	4.00	74.00		1.44	1	39	40							
65.8	67.4	05916	1.6	.6	4GO	4.76	.34	5.30	8.40	101.00		1.78		22	23							
67.4	68.7	05917	1.3	1.3	4EO	4.23	.48	4.40	4.90	89.00		2.13	1	38	39							
68.7	69.9	05918	1.2	1.2	4EO	4.80	.15	6.80	8.10	97.00	90.00	1.17	1	28	29							
69.9	71.3	05919	1.4	1.1	4GO	4.50	.13	6.00	10.80	94.00		1.03		17	17							
96.9	98.9	05920	2.0	2.0	4AO	2.81	.07	.28	.50	5.00												
98.9	100.3	05921	1.4	1.4	4AO	2.74	.06	.24	.30	4.00		.07										
100.3	101.4	05922	1.1	1.1	4AO	2.93	.10	.28	.64	5.00												
110.9	112.1	05923	1.2	1.2	4CL	3.31	.12	1.20	1.33	19.00		.34										
112.1	113.6	05924	1.5	1.5	4CL	3.49	.14	1.78	2.90	25.00		.27										
117.1	119.1	05925	2.0	2.0	4EO	4.35	.28	1.46	2.80	27.00		1.37	2	36	39							
119.1	120.7	05926	1.6	1.6	4EO	4.37	.35	2.60	4.10	48.00		1.51	1	34	36							



DDH: FAGA211

DEPTH FROM	DEPTH TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													S.G. W.R.	
							CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAC %	HG %	MN %	AS %		BA %
53.3	55.3	05735	2.0	2.0	4DE	3.79	.04	8.10	20.10	138.00		1.30	2	13	16						
55.3	57.3	05736	2.0	2.0	4D4	3.62	.07	8.00	18.40	144.00		.69	2	12	14						
57.3	58.6	05737	1.3	1.3	4D4	3.70	.05	6.30	15.60	112.00		.62	1	14	16						
58.6	59.7	05738	1.1	1.1	4E0	4.55	.28	2.70	7.50	62.00		.65	2	34	37						
59.7	60.8	05739	1.1	1.1	4E0	4.82	.12	1.35	2.80	30.00		.82	2	41	44						
60.8	62.4	05740	1.6	1.6	4D4	3.83	.06	7.60	17.70	144.00		.41	2	14	16						
62.4	63.6	05741	1.2	1.2	4C0	3.56	.07	5.00	11.40	92.00		.69		12	12						
63.6	65.1	05742	1.5	1.5	4C0	3.46	.05	3.20	6.10	58.00	56.00	.69	1	12	13						
65.1	66.3	05743	1.2	1.2	4G0	3.62	.02	4.70	10.40	82.00		.62	1	13	14						
66.3	67.6	05744	1.3	1.3	4DE	3.95	.05	6.40	16.40	120.00		1.10	3	15	18						
67.6	68.9	05745	1.3	1.3	4DE	4.20	.10	7.40	16.40	132.00		1.23	3	18	22						
68.9	70.6	05746	1.7	1.7	4E4	4.30	.16	8.20	17.10	134.00		1.92	3	19	22						
70.6	72.0	05747	1.4	1.4	4DA	3.78	.21	6.30	8.60	104.00		2.40	1	17	18						
72.0	73.8	05748	1.8	1.8	4C0	3.64	.26	.20	.45	12.00		1.03	1	24	26						
73.8	75.1	05749	1.3	1.3	4A0	3.21	.15	.08	.51	10.00		.69		15	16						
75.1	76.3	05750	1.2	1.2	4A0	3.31	.18	.08	.54	12.00		.75									
76.3	78.3	05751	2.0	2.0	4CA	3.32	.24	.08	.73	14.00		.89									
78.3	80.3	05752	2.0	2.0	4CA	3.54	.28	.06	.35	14.00		.89									
80.3	81.5	05753	1.2	1.2	4CA	3.55	.22	.14	1.00	17.00		.75	2	21	23						
81.5	83.2	05754	1.7	1.7	4C0	3.51	.31	.06	.33	9.00		.69	2	21	23						
83.2	84.4	05755	1.2	1.2	4CA	3.66	.26	2.20	1.73	162.00	26.00	1.17	2	18	20						
84.4	85.7	05756	1.3	1.3	4CA	3.42	.15	3.20	3.20	45.00		1.17	1	16	18						
85.7	87.7	05757	2.0	2.0	4DA	3.62	.16	6.90	9.50	82.00		1.37	2	15	17						
87.7	89.7	05758	2.0	2.0	4DA	3.37	.08	3.40	4.50	55.00		1.58	1	15	16						
89.7	91.2	05759	1.5	1.5	4A0	3.49	.12	1.29	1.35	18.00		.96	1	19	21						
91.2	92.8	05760	1.6	1.6	4A0	3.19	.13	1.05	1.34	24.00		.69	1	14	16						
92.8	94.5	05761	1.7	1.7	4C0	3.53	.36	.75	.92	14.00		.82	2	21	23						
94.5	96.3	05762	1.8	1.8	4C0	3.56	.26	.43	.40	10.00		.69	2	21	23						
96.3	98.3	05763	2.0	2.0	4A0	3.28	.15	.27	.61	8.00		.55									
98.3	100.3	05764	2.0	2.0	4A0	3.36	.15	.40	.67	12.00		.69									
100.3	102.3	05765	2.0	2.0	4A0	3.38	.18	.95	1.32	22.00		.69									
102.3	104.3	05766	2.0	2.0	4AG	3.21	.16	.07	.28	8.00		.41									
104.3	106.3	05767	2.0	2.0	4A0	3.29	.23	.07	.32	6.00		.48									
106.3	108.3	05768	2.0	2.0	4AG	3.21	.15	.07	.17	6.00		.41									
108.3	110.3	05769	2.0	2.0	4A0	3.48	.53	.10	.24	14.00		.55									
110.3	112.3	05770	2.0	2.0	4A0	2.96	.27	.07	.37	10.00		.27									
112.3	113.0	05771	.7	.7	4AG	3.02	.34	.07	.60	8.00		.34									
113.0	114.0	05772	1.0	1.0	4C0	3.19	.21	.06	.28	8.00		.27									
114.0	116.0	05773	2.0	2.0	4A0	2.89	.09	.06	.33	4.00		.21									
116.0	118.0	05774	2.0	2.0	4A0	2.97	.15	.07	.64	8.00		.27									
118.0	120.0	05775	2.0	2.0	4A0	2.92	.13	.06	.37	6.00		.34									
120.0	122.0	05776	2.0	2.0	4A0	2.85	.04	.01	.64	3.00		.21	2	4	7						
122.0	124.0	05777	2.0	2.0	4A0	3.04	.15	.02	.59	4.00		.34	2	10	13						
124.0	125.7	05778	1.7	1.7	4AG	3.22	.17	1.48	1.11	22.00	20.00	1.10	1	11	12						
125.7	128.0	05779	2.3	2.3	4E0	4.68	.40	2.50	1.16	40.00		1.44	1	40	41						
128.0	129.7	05780	1.7	1.7	4E0	4.67	.33	3.90	1.73	66.00		1.71	1	39	40						
129.7	131.0	05781	1.3	1.3	4E0	4.69	.42	1.41	1.42	30.00		1.58	2	41	43						
131.0	132.3	05782	1.3	1.3	4EC	4.85	.36	1.77	1.58	33.00		1.65	1	42	43						
132.3	134.3	05783	2.0	2.0	4EC	4.03	.23	1.23	1.21	32.00		1.30	2	29	31						
134.3	136.0	05784	1.7	1.7	4EC	3.90	.23	3.20	3.90	56.00		1.71	1	25	26						
136.0	138.0	05785	2.0	2.0	4EA	4.22	.25	3.70	4.10	87.00		1.85	1	26	27						

DDH: FAGA211

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													S.G. W.R.		
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAQ %	HG %	MN %	AS %		BA %	
138.0	140.0	05786	2.0	2.0	4EA	3.79	.29	2.60	4.30	63.00		1.92	1	29	31							
140.0	141.6	05787	1.6	1.6	4EA	4.33	.27	1.14	1.36	26.00		1.17	1	33	34							
141.6	143.3	05788	1.7	1.7	4EA	4.19	.37	3.00	3.60	56.00	50.00	1.78	1	27	28							
143.3	143.8	05789	.5	.5	4D7	3.80	.40	9.00	11.50	141.00		1.17	10	9	19							
174.0	175.8	05790	1.8	1.8	4CE	3.93	.28	2.90	2.50	45.00		.14										
202.0	204.2	05791	2.2	2.2	4G0	4.21	.16	5.50	7.60	86.00		1.51	2	15	17							
204.2	206.2	05792	2.0	2.0	4E8	4.31	.32	3.80	3.29	60.00		1.44	7	27	34							
206.2	208.1	05793	1.9	1.9	4E8	4.14	.34	2.50	2.64	38.00		1.17	8	27	35							

DDH: FAGA212

---DEPTHS---			-----ASSAYS-----																	
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PC %	PY %	TOT FE	BAO %	HG %	MN %	AS %	BA %	S.G. W.R.
67.1	68.4	05794	1.3	1.3	4G0	4.68	.09	4.40	8.34	62.00	.62	1	21	22						
68.4	69.7	05795	1.3	1.3	4G0	4.36	.07	6.20	11.85	104.00	1.17	1	18	19						
69.7	71.0	05796	1.3	1.3	4E4	4.70	.11	4.70	8.90	86.00	1.37		19	20						
71.0	72.3	05797	1.3	1.3	4G0	3.78	.17	8.00	14.20	127.00	1.58		16	17						
72.3	74.1	05798	1.8	1.8	4D0	3.78	.20	5.40	12.30	134.00	1.58	1	14	15						
74.1	74.9	05799	.8	.8	4G0	4.61	.05	3.50	7.70	64.00	.82									
74.9	76.2	05800	1.3	1.3	4DJ	3.78	.07	3.90	19.20	179.00	170.00	1.44	2	8	10					
76.2	77.5	05851	1.3	1.3	4DJ	4.09	.08	7.70	18.40	141.00	1.37	1	17	18						
77.5	79.1	05852	1.6	1.6	4G0	4.63	.07	4.60	8.70	99.00	.89		18	18						
79.1	80.8	05853	1.7	1.7	4G0	4.68	.09	4.50	8.10	98.00	.89		17	17						
80.8	82.8	05854	2.0	2.0	4C0	3.64	.03	2.30	5.70	44.00	.55		15	16						
82.8	83.7	05855	.9	.9	4EJ	4.51	.07	6.80	7.30	114.00	.88	3	14	17						
83.7	85.6	05856	1.9	1.9	4DC	3.52	.06	4.20	9.20	101.00	.75		15	16						
85.6	86.3	05857	.7	.7	4G0	4.53	.04	2.30	5.80	42.00	.48		16	17						
86.3	88.7	05858	2.4	2.4	4E0	4.37	.17	6.20	11.10	127.00	1.30	1	21	23						
88.7	90.1	05859	1.4	1.4	4E0	4.22	.04	5.80	11.10	101.00	1.23	1	26	28						
90.1	91.6	05860	1.5	1.5	4DE	3.78	.06	8.80	13.80	142.00	138.00	.75	2	11	13					
91.6	92.8	05861	1.2	1.2	4EA	3.42	.18	.11	1.09	14.00	.75	2	20	22						
92.8	94.0	05862	1.2	1.2	4EA	3.49	.22	1.44	4.30	32.00	.75	3	17	21						
94.0	96.1	05863	2.1	2.1	4E0	4.56	.23	5.40	11.20	89.00	1.58	3	30	33						
96.1	97.4	05864	1.3	1.3	4DG	3.90	.12	5.10	8.80	86.00	1.23	2	19	22						
97.4	99.4	05865	2.0	2.0	4A0	3.29	.17	1.18	1.80	25.00	.69	1	16	17						
99.4	101.4	05866	2.0	2.0	4A0	3.23	.13	.17	1.22	13.00	.34	1	16	18						
101.4	103.4	05867	2.0	2.0	4A0	2.91	.12	.09	.50	7.00	.27									
103.4	106.1	05868	2.7	2.7	4A0	2.69	.11	.36	.59	13.00	.27									
106.1	108.1	05869	2.0	2.0	4A0	3.11	.16	.39	1.22	13.00	.34									
108.1	110.1	05870	2.0	2.0	4A0	3.02	.11	.32	.81	12.00	.48									
110.1	112.2	05871	2.1	2.0	4A0	3.16	.14	.24	.75	9.00	.34									
112.2	114.2	05872	2.0	2.0	4AE	3.60	.22	.22	.80	11.00	.69									
114.2	116.2	05873	2.0	2.0	4AE	3.63	.23	.35	.91	11.00	.69									
116.2	117.9	05874	1.7	1.7	4AE	3.67	.22	.39	.62	14.00	.62									
117.9	120.0	05875	2.1	2.1	4AE	3.34	.26	.09	.54	13.00	.62									
120.0	122.0	05876	2.0	2.0	4A0	3.02	.20	.05	.46	7.00	.34									
122.0	124.0	05877	2.0	2.0	4A0	3.73	.30	.11	.75	11.00	.34									
124.0	127.1	05878	3.1	3.1	4A0	3.10	.41	.11	.58	12.00	.21									
127.1	129.1	05879	2.0	2.0	4C9	3.30	.22	.33	1.22	10.00	.41									
129.1	131.1	05880	2.0	2.0	4C9	3.21	.65	.04	.78	12.00	.48									
131.1	132.1	05881	1.0	1.0	4C9	3.28	.83	.04	1.38	12.00	.41									
132.1	134.1	05882	2.0	2.0	4A0	3.19	.76	.05	1.51	12.00	.34									
134.1	136.1	05883	2.0	2.0	4A0	3.42	.43	.17	1.10	10.00	.34									
136.1	138.1	05884	2.0	2.0	4A0	3.05	.53	.03	1.10	9.00	.27									
138.1	139.5	05885	1.4	1.4	4A0	3.00	.12	.08	3.93	7.00	.14									
139.5	140.9	05886	1.4	1.4	4A0	3.19	.24	.06	.57	8.00	.34	2	15	17						
140.9	142.1	05887	1.2	1.2	4EC	3.43	.29	.05	1.06	10.00	.48	3	18	21						
142.1	143.2	05888	1.1	1.1	4EC	3.79	.32	2.00	2.90	40.00	1.17	3	26	29						
143.2	145.2	05889	2.0	2.0	4E0	4.56	.42	1.36	3.80	29.00	34.00	1.23	3	31	35					
145.2	147.2	05890	2.0	2.0	4E0	4.67	.28	.90	4.70	20.00	1.17	3	37	41						
147.2	149.2	05891	2.0	2.0	4E0	4.75	.40	.77	2.60	18.00	1.23	3	40	44						
149.2	151.2	05892	2.0	2.0	4E0	4.78	.24	2.40	4.40	35.00	1.30	3	38	41						
151.2	153.2	05893	2.0	2.0	4E0	4.77	.23	3.00	4.89	51.00	1.58	3	37	40						
153.2	154.7	05894	1.5	1.5	4E0	4.75	.36	.90	1.32	23.00	1.58	2	42	44						

DDH: FAGA212

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAO %	HG %	MN %	AS %	BA %	S.G. W.R.
154.7	156.2	05895	1.5	1.5	4E0	4.71	.39	3.50	4.98	59.00		1.30	1	37	39						



DDH: FAGA214

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAC %	HG %	MN %	AS %	BA %	S.G. W.R.
53.0	55.8	11558	2.8	.7	4A4*	3.22	.02	2.70	3.49	44.00	46.00	.34	4	6	10						
67.7	68.3	11559	.6	.5	4AE	3.54	.02	3.89	6.29	69.00		.47	2	5	8						
68.3	69.1	11560	.8	.7	5D*	3.20	.05	2.89	3.29	58.99		1.43	5	1	6						
69.1	69.5	11561	.4	.4	4D4	3.22	.02	3.99	7.70	61.99		1.16	2	2	5						
70.8	71.5	11562	.7	.7	4C0	3.56	.07	1.61	2.50	28.99		.89	2	15	18						
71.8	72.2	11563	.4	.4	4CA	3.08	.08	1.56	1.89	23.00		.68	1	3	5						
74.2	74.7	11564	.5	.5	4D4	3.41	.08	5.70	4.70	61.99		.62	1	7	9						
75.9	76.2	11565	.3	.3	4E4	4.78	.08	11.09	20.19	200.00		1.30	3	15	19						
76.2	76.6	11566	.4	.3	4A0	3.41	.01	.82	1.74	18.00		.47	1	9	10						
76.6	77.0	11567	.4	.3	4E4	4.63	.02	7.29	14.40	135.00	130.00	1.30	1	27	28						
77.0	78.0	11568	1.0	1.0	4A4	3.50	.02	3.00	6.40	55.99		.55	1	9	11						
78.0	79.5	11569	1.5	1.5	4E4*	3.89	.02	5.90	13.69	114.99		.81	2	13	15						
79.5	80.9	11570	1.4	1.4	4E4*	3.99	.08	8.50	15.69	153.00		1.03	2	13	15						
80.9	81.4	11571	.5	.5	4A0	2.99	.02	.22	.38	3.99		.14	1	2	4						
81.4	82.5	11572	1.1	1.1	4E4	4.05	.04	5.50	14.30	110.99		.68	6	15	21						
82.5	84.5	11573	2.0	2.0	4D4	3.18	.02	4.29	11.50	82.00		.20	3	2	5						
84.5	86.5	11574	2.0	2.0	4D4	3.16	.02	3.00	9.40	57.99		.27	3	2	5						
86.5	88.0	11575	1.5	1.5	4D4	3.31	.02	5.20	11.59	104.00		.34	2	2	4						
93.0	93.4	11576	.4	.4	4A41	3.37	.02	2.89	7.70	55.00		.34	2	7	9						
93.4	94.1	11577	.7	.7	4A0	3.04	.01	.11	.29	3.00		.07	1	3	4						
94.1	94.7	11578	.6	.6	4E4	4.46	.01	1.64	6.70	22.00	26.00	.81	1	34	35						
94.7	95.4	11579	.7	.7	4A14	3.20	.01	3.89	11.69	62.99		.27	1	1	3						
95.4	96.8	11580	1.4	1.4	4A0	2.95	.01	.08	.17	3.00		.07	2	1	3						
98.6	100.6	11581	2.0	2.0	4A0	2.95	.01	.70	1.45	15.99		.07	2	1	3						
100.6	102.1	11582	1.5	.9	4A0	2.98	.01	1.12	3.29	22.00		.14	1	1	2						
180.8	182.8	11583	2.0	2.0	5A19		.01	.02	.08	3.00											
182.8	184.8	11584	2.0	2.0	5A19		.01	.05	.08	3.00											
184.8	186.8	11585	2.0	1.8	5A19		.01	.05	.11	3.00											
186.8	188.9	11586	2.1	1.7	5A19		.01	.02	.04	.99											
291.1	293.7	11776	2.6	2.6	4GE4	4.46	.24	9.59	12.40	150.00		2.60	1	20	21						
293.7	295.9	11777	2.2	2.2	4DC	2.98	.04	1.23	2.50	25.00		.55	3	4	7						
295.9	297.3	11778	1.4	1.4	4L14	2.87	.02	.59	.73	6.00		.47	2	1	3						
321.2	325.5	11779	4.3	1.6	4E4	3.47	.02	2.10	3.20	40.00		.68	1	15	17						
325.5	327.2	11780	1.7	1.7	4A4	3.31	.07	2.20	3.89	44.00		1.10	2	13	15						

DDH: FAGA215

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													S.G. W.R.	
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAO %	HG %	MN %	AS %		BA %
61.7	63.7	12251	2.0	.9	4A0		.01	.04	.09	3.00											
63.7	65.7	12252	2.0	1.5	4A0		.01	.01	.05	1.00											
65.7	67.0	12253	1.3	1.3	4A0		.01	.20	.41	5.00											
67.0	69.0	12254	2.0	1.7	4A0		.01	.06	.55	3.00											
69.0	71.0	12255	2.0	1.8	4A0		.01	.01	.10	1.00											
71.0	72.4	12256	1.4	1.4	4A0		.01	.01	.06	1.00											
72.4	73.8	12257	1.4	1.1	4A0		.01	.52	.77	11.00											
75.4	76.1	12258	.7	.6	4D0	3.21	.01	1.97	7.50	34.00		.27	5	5	11						
76.1	77.0	12259	.9	.9	4C0	3.06	.01	1.88	3.40	29.00		.21	3	3	7						
77.0	77.8	12260	.8	.8	4D0	3.15	.04	4.60	9.70	94.00	100.00	.41	6	6	12						
77.8	78.3	12261	.5	.5	4E0	4.29	.04	2.31	9.60	57.00		.96	10	20	30						
78.7	79.7	12262	1.0	.7	4E0	4.42	.08	1.94	3.30	39.00		.55	17	22	39						
79.7	80.3	12263	.6	.6	4A0	3.46	.03	.94	3.40	23.00		.34	7	8	16						
80.3	82.2	12264	1.9	.9	4D4	3.16	.02	2.40	6.10	42.00		.41	4	6	10						
82.2	83.1	12265	.9	.7	4A4	3.57	.02	.84	5.40	20.00		.21	9	6	16						
83.1	85.1	12266	2.0	1.8	5A1		.01	.04	.33	5.00											
85.1	86.3	12267	1.2	1.1	5A1		.01	.01	.20	6.00											
99.8	101.0	12268	1.2	1.2	4A13	3.50	.08	4.00	6.50	64.00		1.10	1	12	14						
101.5	102.4	12269	.9	.6	4L12	3.28	.05	.82	1.53	15.00		.48	3	10	14						
102.8	103.3	12270	.5	.5	4D0	3.53	.03	3.50	6.90	47.00		.55	3	10	14						
103.7	105.2	12271	1.5	1.4	4A4	3.08	.01	2.50	5.40	36.00		.55	1	2	3						
105.2	106.6	12272	1.4	1.4	4A4	3.12	.02	2.32	4.20	40.00		.75	2	2	4						
106.6	107.3	12273	.7	.6	4C0	4.14	.03	.74	3.30	15.00		.41	4	9	13						
107.3	108.5	12274	1.2	1.2	4A14	3.29	.04	1.93	3.70	35.00		.89	1	12	13						
108.5	110.3	12275	1.8	1.8	4L0	3.22	.02	.66	1.49	13.00		.34	3	3	6						
110.3	111.8	12276	1.5	1.5	4L0	3.18	.07	.95	1.42	18.00		.34	4	6	10						
111.8	112.8	12277	1.0	1.0	4L0	3.50	.04	1.18	1.51	23.00		.41	4	13	18						
112.8	113.5	12278	.7	.7	4C3	3.66	.05	2.12	3.40	36.00		1.17	2	17	20						
113.5	114.4	12279	.9	.8	4L3	3.10	.02	1.01	1.95	21.00		.55	4	6	10						
114.4	115.8	12280	1.4	1.3	5C4*	3.68	.05	10.80	16.90	155.00	144.00	.48	7	5	13						
119.3	120.9	12281	1.6	1.6	4L14	3.18	.04	1.62	3.00	30.00		.75	4	7	12						
120.9	122.0	12282	1.1	1.0	4L0	3.12	.07	.14	.82	10.00		.27	5	3	9						
122.0	123.0	12283	1.0	.9	4A14	3.21	.06	2.18	4.50	50.00		.62	4	6	11						
123.0	123.3	12284	.3	.3	4D4	3.31	.06	2.92	7.50	46.00		.75	2	10	12						
123.3	125.3	12285	2.0	1.9	4A14	3.51	.07	6.61	12.70	106.00		1.30	1	7	9						
127.3	129.1	12286	1.8	1.8	4A14	3.27	.05	3.94	7.70	63.00		.96	1	9	11						
129.1	131.1	12287	2.0	1.9	4A13	3.12	.07	1.32	2.80	24.00		1.03	1	12	13						
131.1	132.3	12288	1.2	1.1	4A13	3.02	.03	1.92	2.70	36.00		.82	1	8	9						
143.9	146.7	12289	2.8	2.2	4A*		.01	.07	.14	4.00											
160.0	160.6	12290	.6	.6	4A0		.01	.01	.04	3.00											
160.6	161.8	12291	1.2	1.1	5A19		.02	.64	2.20	15.00											
161.8	162.4	12292	.6	.5	4D0		.02	1.55	4.70	27.00											
210.8	212.1	12293	1.3	1.2	4A0	2.86	.01	.01	.05	3.00		.14	2	1	3						
212.1	213.4	12294	1.3	1.3	4A0	2.97	.02	.46	.73	10.00		.27	1	2	4						
213.4	213.9	12295	.5	.5	4E4*	3.80	.13	6.60	9.90	133.00		1.44	3	16	19						
213.9	214.7	12296	.8	.8	4E4*	4.60	.16	12.30	22.00	161.00		2.06	1	20	21						
214.7	215.0	12297	.3	.3	4L*	3.96	.02	1.04	2.70	18.00		.48	2	6	9						
215.0	215.4	12298	.4	.3	4K4	4.20	.06	4.90	11.70	90.00		1.37	2	23	25						
215.4	215.7	12299	.3	.3	4A0	3.98	.07	6.80	14.50	118.00		1.30	1	18	20						
215.7	217.3	12300	1.6	1.5	4G4*	4.48	.06	4.90	10.10	93.00	93.00	1.30		15	16						
217.3	219.3	12301	2.0	1.4	4G4*	4.51	.08	4.10	8.00	70.00		1.17		15	16						















DDH: FAGA228

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAC %	HG %	MN %	AS %	BA %
52.8	54.8	12439	2.0	1.9	4D5	2.85	.02	2.02	5.76	40.00		.20	1		1					
54.8	56.0	12440	1.2	1.0	4D5	2.87	.04	1.82	6.54	46.00		.20	1		1					
56.0	58.0	12441	2.0	1.9	4D0	2.87	.02	2.08	5.76	41.00		.27	1		1					
58.0	60.1	12442	2.1	2.1	4D0	2.91	.05	3.24	6.48	46.00		.40	1	1	2					
60.1	61.0	12443	.9	.9	4D0	2.99	.08	3.52	2.41	45.00		.75	1	5	6					
61.0	63.0	12444	2.0	1.4	4D0	2.93	.04	2.95	3.16	38.00		.89		2	3					
63.0	65.3	12445	2.3	1.8	4D0	2.91	.05	2.64	5.36	40.00		.40	1	2	4					
65.3	67.9	12446	2.6	2.0	4C5	2.93	.07	1.41	3.24	24.00		.47	1	4	5					
67.9	69.9	12447	2.0	1.5	4CA	2.83	.05	1.11	2.64	20.00		.47		2	3					
69.9	71.1	12448	1.2	.7	4CA	2.87	.04	.88	2.64	17.00		.40		3	4					
71.1	72.8	12449	1.7	1.6	4C5	2.87	.05	1.20	2.50	18.00		.47	1	3	4					
85.2	87.2	12450	2.0	2.0	4A0		.02	.36	.72	9.00										
87.2	88.7	12451	1.5	1.4	4A1	3.12	.02	1.58	2.75	33.00		.40	2	7	10					
88.7	90.5	12452	1.8	1.8	4A41	3.20	.02	3.85	6.59	86.00		.55	2	7	9					
90.5	91.3	12453	.8	.7	4A0	3.29	.02	1.88	2.14	35.00		.01	1	11	13					
91.3	93.5	12454	2.2	2.0	4A14	3.25	.02	2.75	4.25	58.99		.20	2	8	10					
95.8	97.2	12455	1.4	1.4	4JD7	4.01	.05	12.90	22.69	369.00		1.23	12	3	16					
118.0	119.0	12456	1.0	.9	4G4	4.23	.10	6.33	9.11	116.99		1.37	3	23	26					
121.5	122.0	12457	.5	.5	4D4		.05	7.36	7.25	105.00										
125.3	126.5	12458	1.2	1.2	4A4	3.29	.04	4.69	10.30	78.00		.89	2	8	10					
128.1	130.5	12459	2.4	2.3	4A4	3.31	.02	2.79	6.62	54.00		.75	2	7	10					
132.3	133.6	12460	1.3	1.3	4D0	3.33	.02	3.16	6.79	67.00		.40	3	8	12					
133.6	135.7	12461	2.1	2.1	4A4	3.27	.02	2.14	5.13	42.00		.55	2	11	13					
135.7	137.7	12462	2.0	2.0	4A4	3.62	.02	3.83	8.50	86.00		1.10	1	16	18					
137.7	139.2	12463	1.5	1.5	4A0	3.45	.02	1.44	3.31	31.99		.01	2	17	19					
139.2	141.0	12464	1.8	1.7	4A4	3.25	.02	2.45	4.99	42.00		.55		11	11					
143.6	145.8	12465	2.2	2.0	4AE	3.08	.02	1.73	4.19	28.99		.47	3	4	7					

DDH: FAGA229

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT.	AG(FA) G/MT	AU(FA) G/MT	PC %	PY %	TOT. FE	BAG %	HG %	MN %	AS %	BA %	S.G. W.R.
103.0	104.8	12466	1.8	.0	4A4	2.95	.01	1.38	5.40	28.99		.14	1	3	5						
104.8	105.5	12467	.7	.0	4CO	2.99	.01	.72	2.73	14.99		.14	3		4						
105.5	107.3	12468	1.8	.0	4A0	2.89	.02	.88	2.33	18.00		.01	2	1	3						
107.3	108.8	12469	1.5	.0	4A0	2.87	.02	.82	1.55	13.99		.07	1	1	2						

DDH: FAGA230

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													S.G. W.R.		
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAC %	HG %	MN %	AS %		BA %	
83.7	85.4	12470	1.7	1.6	4EDH	4.25	.02	.78	2.91	21.00		.62	4	30	34							
85.7	87.5	12471	1.8	1.6	4EDH	4.17	.02	2.50	10.19	29.99		.55	5	23	28							
90.4	92.5	12472	2.1	2.0	4A4	3.04	.02	2.60	6.29	42.00		.27	2	3	5							
92.5	94.3	12473	1.8	1.8	4A4	3.02	.05	3.47	6.50	57.99		.27	2	2	4							
102.7	103.3	12474	.6	.5	4A4	3.04	.11	2.22	5.50	43.00		.55	1	3	5							
103.3	105.7	12475	2.4	2.3	4D0	3.16	.02	1.46	3.81	27.99		.14	4	4	8							
105.7	107.7	12476	2.0	1.9	4A4	3.06	.04	2.60	5.28	48.00		.34	1	4	5							
107.7	109.7	12477	2.0	2.0	4A4	3.02	.02	2.25	3.85	35.00		.34	1	2	3							
109.7	111.5	12478	1.8	1.5	4A4	3.22	.02	1.58	4.67	25.00		.34	1	7	8							
114.1	115.8	12479	1.7	1.7	4A0		.02	.40	2.02	10.00												
117.9	119.8	12480	1.9	1.8	4A4	3.16	.02	4.62	6.16	70.00		.55	1	5	6							
119.8	121.6	12481	1.8	1.7	4A4	3.12	.04	3.22	5.98	48.00		.40	1	5	6							
136.8	138.1	12482	1.3	1.1	4A4	3.56	.02	2.33	4.88	28.99		.20	3	14	18							
139.6	142.4	12483	2.8	2.6	4A4	3.12	.02	3.66	7.79	63.99		.40	2	5	8							
143.0	144.2	12484	1.2	1.0	4DA	3.00	.01	1.55	5.29	25.00		.14	2	4	6							
147.8	149.2	12485	1.4	1.4	4A4	3.49	.02	3.83	9.84	83.00		.07	4	9	14							
150.2	151.0	12486	.8	.7	4A0	3.02	.01	2.06	6.00	44.00		.14	3	2	6							
153.0	155.1	12487	2.1	1.4	4A4	3.35	.01	4.75	11.30	90.00		.20	2	6	9							
162.0	165.1	12488	3.1	2.7	4A4	3.02	.01	1.38	4.21	27.99		.20	1	6	7							
165.6	167.9	12489	2.3	2.0	4A0	2.91	.02	1.03	2.16	17.00		.14	3	1	5							

DDH: FAGA231

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAC %	HG %	MN %	AS %	BA %	S.G. W.R.
117.8	119.3	12608	1.5	1.1	4A4	3.25	.02	3.12	7.87	55.99		.40	3	1	5						
119.3	120.7	12609	1.4	1.4	4A4	3.60	.02	5.13	11.84	115.99		.55	3	2	5						
121.0	122.7	12610	1.7	1.7	4A4	3.39	.02	3.60	8.48	81.00		.27	1	2	3						
123.3	123.9	12611	.6	.6	4A4		.02	2.95	7.87	71.00											
152.2	154.0	12612	1.8	1.8	4A4	3.60	.02	2.85	9.61	58.99		.40	6	2	9						
154.0	155.6	12613	1.6	1.5	4A4	3.27	.02	3.04	6.58	59.99		.27	1	2	4						
155.6	157.3	12614	1.7	1.6	4A4	3.27	.02	2.08	6.65	46.00		.14	2	1	3						
157.3	159.3	12615	2.0	.0	4A4	3.18	.02	1.56	5.66	38.00		.34	1		2						
159.3	161.1	12616	1.8	.0	4A4	3.18	.01	1.59	6.29	39.00		.27	2	1	3						
164.2	165.4	12617	1.2	.0	4A0	3.39	.01	.81	3.54	15.99		.27	5	1	6						
165.4	167.6	12618	2.2	.0	4A4	3.22	.02	2.16	3.85	45.00		.40	2	1	3						
172.4	173.7	12619	1.3	.0	4A0	3.16	.01	1.12	3.02	34.00		.20	1	1	2						
173.7	174.9	12620	1.2	.0	4A4	3.25	.01	1.74	6.70	46.00		.20	1	2	4						

DDH: FAGA232

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PC %	PY %	TOT FE	BAC %	HG %	MN %	AS %	BA %
75.6	77.1	12628	1.5	1.5	4C0		.05	2.16	2.14	30.99										
89.4	91.5	12629	2.1	2.0	4A0	3.33	.02	1.17	2.19	22.00		.14	2	3	5					
91.5	92.8	12630	1.3	1.2	4A0	3.29	.02	.99	1.82	20.00		.34	4	3	8					
97.1	100.9	12631	3.8	1.5	4A0	3.29	.02	.97	2.52	19.00		.20	3	4	7					
107.3	108.8	12632	1.5	1.4	4A0	3.43	.02	1.53	2.93	35.00		.55	8	1	10					
108.8	110.2	12633	1.4	1.3	4A4	3.35	.02	1.99	3.81	45.00		.55	7	1	9					
115.6	116.1	12634	.5	.5	4C0		.01	.98	2.75	18.00										
118.7	120.7	12635	2.0	2.0	5D*		.01	.58	1.78	12.00										
121.6	123.0	12636	1.4	1.3	4A4	3.20	.02	1.13	6.41	37.00		.20	2	1	4					
123.0	124.4	12637	1.4	1.3	4A4	3.18	.01	1.77	6.41	43.00		.14	1	1	3					
124.4	126.4	12638	2.0	2.0	4D4	3.35	.01	3.04	10.00	62.99		.07		2	2					
126.4	127.9	12639	1.5	1.5	4D0	3.18	.01	1.63	7.99	23.00		.07	1	1	3					
127.9	129.9	12640	2.0	2.0	4A4	3.16	.01	1.63	6.34	34.00		.07	1	1	2					
129.9	131.6	12641	1.7	1.7	4A4	3.24	.02	1.47	5.04	30.99		.20	4	1	5					
132.7	135.3	12642	2.6	1.5	4A4	3.39	.01	2.66	6.99	53.00		.27	8	2	11					
135.3	137.9	12643	2.6	.7	4A4	3.25	.01	2.39	5.70	54.00		.14	1	1	2					
139.3	141.3	12644	2.0	1.9	4A4	3.20	.01	2.10	5.34	48.00		.20		1	2					
141.3	143.3	12645	2.0	2.0	4A0	3.10	.01	1.40	3.89	27.99		.27	2		3					
143.3	145.3	12646	2.0	2.0	4A4	3.27	.01	1.82	5.00	30.99		.40	3		4					
145.3	147.8	12647	2.5	2.4	4A4	3.20	.01	2.22	6.24	42.00		.34	1	1	3					
147.8	149.8	12648	2.0	1.9	4A4	3.20	.01	1.74	4.09	39.00		.14	1	2	4					
149.8	151.8	12649	2.0	1.9	4A0	3.12	.02	1.01	3.39	21.00		.14	2	2	5					
151.8	153.2	12650	1.4	1.4	4A4	3.29	.02	2.12	5.83	44.00		.27	4	2	6					
153.2	155.2	12651	2.0	2.0	4A4	3.16	.02	1.51	4.09	29.99		.34	2	1	4					
155.2	157.2	12652	2.0	2.0	4A0	3.24	.04	2.12	2.73	29.99		.55	5		6					
157.2	158.7	12653	1.5	1.5	4A4	3.45	.02	2.29	5.25	39.00		.68	8	1	9					
158.7	160.8	12654	2.1	2.1	4A0	3.24	.04	1.36	2.62	26.00		.27	4	2	7					
160.8	163.0	12655	2.2	2.2	4A0	3.64	.02	1.05	3.08	22.00		.27	16	1	18					
163.0	165.0	12656	2.0	2.0	4A0	3.29	.02	1.41	3.31	25.00		.40	8		9					
165.0	167.0	12657	2.0	2.0	4A4	3.33	.02	2.12	3.41	39.00		.47	8	1	9					
167.0	168.9	12658	1.9	1.9	4A4	3.08	.02	1.45	3.85	34.00		.20	2		3					
168.9	171.0	12659	2.1	1.8	4A0	3.35	.02	1.74	2.58	33.00		.34	7	1	9					
171.0	172.0	12660	1.0	.9	4A0	3.20	.02	1.61	2.35	30.99		.40	6		7					
172.0	174.1	12661	2.1	2.0	4A0	3.60	.07	1.82	3.14	33.00		.47	15	1	16					
174.1	175.1	12662	1.0	1.0	4A34	3.54	.05	3.77	6.66	65.00		.62	11	2	13					
175.1	177.0	12663	1.9	1.7	5D4*	3.14	.02	.83	2.46	13.99		.01		5	5					
177.0	178.5	12664	1.5	1.5	4A0	3.12	.01	1.06	3.54	18.00		.14	8	1	9					
179.8	181.3	12665	1.5	1.4	4A0	3.06	.01	.85	2.81	18.00		.07	1	2	3					
181.3	182.8	12666	1.5	1.4	4A0	3.10	.01	.61	.90	11.00		.01	2	1	3					
182.8	184.8	12667	2.0	2.0	4A4	3.12	.02	1.13	3.91	23.00		.07	2	1	4					
184.8	186.8	12668	2.0	1.4	4A0	3.14	.02	2.29	5.17	33.00		.47	2	1	3					
186.8	188.8	12669	2.0	1.7	4A0	3.10	.02	.98	3.85	23.00		.07	2	2	4					
188.8	190.0	12670	1.2	1.0	4A4	3.35	.01	.95	3.45	23.00		.07	2	2	4					
190.0	191.5	12671	1.5	1.0	4A4	3.12	.01	.95	2.25	13.00		.07		4	5					

DDH: FAGA233

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAO %	HG %	MN %	AS %	BA %
102.4	106.7	12672	4.3	4.3	4A0	3.16	.02	1.43	2.93	27.99		.20	3	7	11					
108.1	108.5	12673	.4	.4	4E4	4.45	.05	3.97	8.60	63.99		.47	4	28	32					
109.3	110.8	12674	1.5	1.5	4A4D	3.20	.07	4.46	3.95	71.00		.47	2	9	11					
110.8	113.0	12675	2.2	2.2	4A4	3.04	.02	3.60	5.11	55.00		.47	1	4	6					
113.0	115.1	12676	2.1	2.1	4AC3	3.24	.04	2.37	3.35	44.00		.28	2	11	13					
116.8	117.7	12677	.9	.9	4D0	3.08	.01	1.88	4.30	33.00		.14	4	5	10					
121.0	122.6	12678	1.6	1.6	4DE	3.45	.02	3.04	6.12	59.99		.47	7	9	17					
123.0	124.2	12679	1.2	1.2	4E4	3.91	.07	8.50	10.30	138.00		.47	7	14	21					
124.7	125.1	12680	.4	.4	4D4	3.39	.07	6.76	10.00	89.00		.34	5	5	10					
127.0	128.6	12681	1.6	1.6	4A4	3.02	.02	2.27	6.94	46.00		.28	2	3	6					
130.1	131.4	12682	1.3	1.3	4E0	4.40	.01	.28	1.59	13.99		.20	3	36	40					
134.1	134.8	12683	.7	.7	4EA	4.29	.04	11.26	16.50	209.00		1.16	2	18	20					
159.1	160.8	12684	1.7	1.2	4DEA	3.50	.05	7.20	12.09	133.00		.47	4	8	12					
169.1	170.2	12685	1.1	1.1	4E4	3.49	.02	1.83	4.58	36.00		.47	3	15	18					
170.2	173.6	12686	3.4	3.4	4A4	2.98	.02	1.41	3.70	25.00		.34	3	3	6					
175.5	177.4	12687	1.9	1.9	4A4	3.22	.05	4.17	5.50	87.00		.68	1	7	9					
177.4	179.4	12688	2.0	2.0	4A4	3.49	.08	5.36	8.96	127.99		.81	1	9	11					
180.9	184.1	12689	3.2	2.8	4A0	2.99	.01	.84	1.44	14.99		.20	2	5	7					

DDH: FAGA234

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													S.G. W.R.		
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAC %	HG %	MN %	AS %		EA %	
76.6	79.1	12690	2.5	2.5	4E4	4.33	.01	1.65	5.42	28.99		.89	2	30	32							
79.8	80.1	12691	.3	.3	4E4		.02	3.70	7.91	56.99												
83.7	84.0	12692	.3	.3	4E0		.02	.83	1.62	17.00												
84.0	86.9	12693	2.9	2.3	4A0		.02	.93	1.55	18.00												
86.9	89.1	12694	2.2	2.2	4E0	3.74	.05	7.63	13.50	134.00		1.16	2	12	15							
91.1	91.8	12695	.7	.5	4D4		.02	5.16	9.30	115.99												
96.3	98.1	12696	1.8	1.4	4DA	3.45	.08	3.89	5.07	57.99		1.30	2	14	16							
103.8	105.0	12697	1.2	1.1	4DE4	4.08	.10	8.10	15.19	127.99		.95	3	17	20							
105.0	107.5	12698	2.5	2.5	4DA	3.02	.02	1.89	4.98	29.99		.40	3	3	6							
110.4	112.6	12699	2.2	1.8	4D4	3.56	.05	7.41	11.00	152.00		.55	6	5	11							
112.6	114.6	12700	2.0	2.0	4A0	3.02	.02	1.65	2.91	30.99		.62	5	2	7							
120.6	125.0	12701	4.4	1.9	4A0	3.06	.02	.64	1.24	15.99		.20	1	7	9							
125.5	128.2	12702	2.7	2.7	4A4	2.91	.02	3.12	2.91	33.00		.47	1	1	3							



DDH: FAGA236

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													S.G. W.R.	
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAC %	HG %	MN %	AS %		BA %
65.6	67.6	12720	2.0	2.0	4A4	3.27	.04	1.92	3.08	39.00		.40	8	1	10						
67.6	69.6	12721	2.0	2.0	4A0	3.08	.04	.44	.68	11.00		.34	5	1	7						
69.6	71.6	12722	2.0	2.0	4A0	2.95	.02	1.08	1.62	19.00		.34	4	1	5						
71.6	73.8	12723	2.2	2.0	4A4	3.06	.02	1.80	3.91	31.99		.47	6	1	7						
73.8	75.6	12724	1.8	1.8	4C0	3.00	.02	1.17	3.20	22.00		.34	3	2	6						
75.6	77.4	12725	1.8	1.8	4C0	3.10	.02	1.25	2.91	22.00		.62	4	1	6						
77.4	79.2	12726	1.8	1.8	4D0	3.16	.05	1.88	3.83	28.99		.47	9	1	10						
88.1	89.2	12727	1.1	1.1	4AD	3.06	.05	2.29	4.21	31.99		.27	2	2	4						
93.9	95.3	12728	1.4	1.4	4A4	3.10	.02	1.60	4.17	27.99		.27	4	2	7						
95.3	96.9	12729	1.6	1.6	4A0	2.95	.02	1.62	2.81	25.00		.34	3		4						
96.9	98.5	12730	1.6	1.6	4A0	2.95	.02	1.08	3.24	20.00		.27	2	2	4						
98.5	99.3	12731	.8	.8	4D0	2.97	.02	1.30	3.08	24.00		.14	1	2	4						
100.3	101.0	12732	.7	.7	4AD	3.08	.02	2.68	5.79	46.00		.14	2	3	5						
101.0	103.1	12733	2.1	2.1	4A4	3.10	.05	2.14	3.14	36.00		.27	5	1	7						
103.1	105.2	12734	2.1	1.8	4A0	3.10	.05	1.69	3.08	33.00		.40	5	1	6						
105.2	107.3	12735	2.1	1.2	4A4	3.08	.04	3.00	7.59	60.99		.55	2	1	4						
107.3	109.4	12736	2.1	1.0	4A4	3.00	.04	2.37	5.09	44.00		.40	2	1	3						
109.4	110.6	12737	1.2	1.2	4D0	3.04	.04	1.78	4.28	31.99		.55	3	3	6						
110.6	111.5	12738	.9	.1	4A4	2.98	.04	1.93	4.30	36.00		.07	1	3	4						
111.5	112.8	12739	1.3	1.1	4A4	3.08	.02	2.41	4.87	36.00		.07	3	3	6						
112.8	114.0	12740	1.2	1.2	4AD	3.00	.02	1.59	3.58	27.00		.01	1	3	4						
114.6	117.0	12741	2.4	2.4	4D4	3.20	.04	3.22	6.50	50.00		.20	5	2	7						
117.0	118.5	12742	1.5	1.5	4E4	4.28	.05	3.33	8.10	67.00		.75	24	3	28						
119.2	120.1	12743	.9	.1	4E0		.01	.29	1.41	17.00											
122.5	124.0	12744	1.5	1.4	4C0	2.95	.05	1.62	2.25	25.00		.14	3	3	6						
124.0	126.4	12745	2.4	2.0	4A4	3.16	.04	2.14	3.22	36.00		.62	9		10						
126.4	128.8	12746	2.4	2.2	4A4	3.10	.04	2.12	3.68	33.00		.75	5		6						
128.8	131.2	12747	2.4	2.1	4A4	3.16	.05	3.02	2.60	43.00		1.30	7		8						
131.2	133.8	12748	2.6	2.2	4A0	3.04	.14	1.78	2.60	28.99		.62	7		7						
134.7	136.2	12749	1.5	1.3	4A34		.02	4.02	4.88	71.00											
136.8	138.1	12750	1.3	1.2	4DA		.04	2.39	4.29	40.00											
138.9	140.5	12751	1.6	1.6	4A4	3.12	.02	3.04	6.29	52.00		.68	6	1	8						
140.5	142.2	12752	1.7	1.7	4A4	2.95	.02	1.93	4.94	39.00		.20	1	1	3						
142.2	143.4	12753	1.2	1.1	3G96	2.95	.02	1.47	1.74	24.00		.27	1	1	2						
143.4	144.8	12754	1.4	1.4	3G46	2.93	.14	1.25	2.21	14.99		.27	1	1	3						
146.1	147.0	12755	.9	.7	4CH		.02	2.24	3.77	44.00											
147.0	148.1	12756	1.1	1.1	3G96		.02	.69	2.20	13.00											
154.8	156.1	12757	1.3	1.3	4D5		.05	1.42	2.31	24.00											
157.1	158.1	12758	1.0	1.0	5D4*9		.02	.80	1.02	13.99											
158.1	160.1	12759	2.0	2.0	4C5	3.10	.05	1.62	3.12	29.99		.40	2	5	7						
161.9	164.0	12760	2.1	2.1	4A4	3.16	.02	2.54	4.42	43.00		.47	2	7	10						
164.0	166.1	12761	2.1	1.9	4A4	3.16	.04	2.21	5.09	36.00		.47	1	5	7						
290.9	292.4	12762	1.5	1.5	4G4#	4.16	.11	4.82	9.32	97.00		1.03	1	18	19						
357.3	359.0	12763	1.7	1.7	4EGL	3.91	.08	3.91	5.23	54.00		.68	2	13	15						
360.0	361.1	12764	1.1	1.0	4G4	4.57	.14	6.23	6.62	89.00		1.51	3	21	24						
361.1	363.0	12765	1.9	1.8	4E0*	4.63	.23	1.65	1.25	24.00		1.64	5	35	40						
363.5	364.7	12766	1.2	1.1	4ELD		.11	.68	.46	13.00											
364.7	365.9	12767	1.2	1.2	4G4	4.50	.11	5.24	5.92	66.00		.95	5	18	23						
365.9	367.9	12768	2.0	2.0	4C79	3.74	.27	1.26	1.87	22.00		.20	10	17	27						
367.9	369.8	12769	1.9	1.9	4C79	3.37	.36	.76	1.85	17.00		.27	7	9	16						

DDH: FAGA237

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PG %	PY %	TOT FE	BAG %	HG %	MN %	AS %	BA %	S.G. W.R.
78.5	80.5	12782	2.0	1.2	4A4	3.02	.05	2.87	6.50	47.00		.34	2	2	4						
80.5	82.5	12783	2.0	1.9	4A0	2.97	.02	.88	1.65	18.00		.40	2	2	4						
82.5	85.1	12784	2.6	2.0	4A0	2.91	.02	1.02	2.08	17.00		.20	1	2	3						
85.8	89.8	12785	4.0	1.5	4A4	2.99	.02	2.35	4.92	43.00		.34	1	1	2						
89.8	91.8	12786	2.0	1.6	4A4	3.06	.04	2.70	5.09	37.00		.68	1	4	5						
91.8	93.8	12787	2.0	1.2	4A4	2.91	.02	2.00	4.69	39.00		.27		1	2						
93.8	95.8	12788	2.0	.7	4A0	2.87	.01	.76	2.06	17.00		.27		1	1						
95.8	97.8	12789	2.0	.6	4A4	2.91	.01	1.15	4.75	26.00		.27		1	2						
97.8	99.8	12790	2.0	.4	4A4	2.95	.01	2.25	4.21	38.00		.34	2		2						
99.8	102.3	12791	2.5	2.1	4A4	3.18	.08	5.20	9.09	82.00		.81	2	3	5						
102.3	104.4	12792	2.1	2.0	4DC5	3.10	.08	3.83	4.76	50.00		.75	2	3	6						
104.4	105.8	12793	1.4	1.3	4L41		.07	.23	.48	6.99											
105.8	107.8	12794	2.0	2.0	4C5	3.00	.05	1.25	2.10	25.00		.81	1	4	5						
107.8	109.8	12795	2.0	2.0	4C5		.05	.56	1.33	12.00											
109.8	111.8	12796	2.0	2.0	4C5		.04	.98	1.67	18.00											
111.8	113.7	12797	1.9	1.9	4C5	2.99	.04	1.17	1.77	20.00		.40	2	4	6						
129.6	131.6	12798	2.0	2.0	4C5		.05	.68	1.46	15.99											
131.6	133.6	12799	2.0	2.0	4C5	2.93	.07	1.23	2.62	26.00		.55	1	3	5						
133.6	135.5	12800	1.9	1.9	4C5	2.95	.05	1.06	2.64	22.00		.40	1	3	4						
135.5	137.5	12801	2.0	2.0	4A4	3.02	.05	1.80	4.48	36.00		.40	1	4	6						
137.5	139.5	12802	2.0	1.4	4A4	3.02	.05	2.52	6.70	50.00		.55	1	4	5						
139.5	141.0	12803	1.5	1.2	4A4	3.04	.02	2.25	6.90	50.00		.40	1	3	5						
141.0	142.3	12804	1.3	1.3	4A0	2.95	.05	1.29	3.50	28.99		.40	1	3	4						
181.8	183.8	12805	2.0	1.4	4A0	2.99	.02	.99	2.14	19.00		.40	2	3	6						
183.8	185.5	12806	1.7	1.4	4A4	2.93	.04	1.82	4.11	28.99		.47	1	1	2						
186.8	188.1	12807	1.3	1.3	4A4	3.00	.02	2.60	5.90	55.00		.34	2	1	3						
194.5	195.6	12808	1.1	1.0	4A0	3.06	.02	.93	2.81	20.00		.14	2	5	7						
195.6	197.3	12809	1.7	1.7	4E45	4.25	.02	3.08	8.90	63.99		.47	2	25	27						
200.1	202.2	12810	2.1	2.0	4A0	3.00	.02	1.25	2.62	24.00		.34	2	3	6						

DDH: FAGA238

						-----ASSAYS-----															
DEPTHS	SAMPLE	INT.	REC.	ROCK	S.G.	CU	PB	ZN	AG(AA)	AG(FA)	AU(FA)	PO	PY	TOT	BAC	HG	MN	AS	BA	S.G.	
FROM	TO	NO.		UNIT	PULP	%	%	%	G/MT	G/MT	G/MT	%	%	FE	%	%	%	%	%	W.R.	
48.5	49.9	12770	1.4	1.0	4C5		.01	.23	.33	7.99											
49.9	51.6	12771	1.7	1.6	4C5	3.06	.05	.81	1.94	20.00		.20	9	1	11						
51.6	54.5	12772	2.9	2.0	4C5	3.08	.08	.61	1.60	15.99		.20	8		9						
54.5	56.5	12773	2.0	2.0	4C5	3.02	.08	.56	1.62	15.99		.34	9		10						
56.5	58.5	12774	2.0	1.8	4C5	3.08	.07	.54	1.88	17.00		.34	8		9						
58.5	61.3	12775	2.8	2.2	4C5	2.98	.05	.99	1.96	21.00		.47	4		5						
61.3	63.3	12776	2.0	1.9	3G14		.02	.20	.31	6.00											
63.3	65.8	12777	2.5	2.3	3G14		.08	.77	1.44	15.99											
65.8	67.8	12778	2.0	2.0	4L14		.05	.62	.88	13.00											
67.8	69.9	12779	2.1	1.9	4L14		.04	.68	.84	13.99											
89.3	89.9	12780	.6	.6	4E4#		.14	5.50	10.09	130.00											
96.2	98.8	12781	2.6	1.1	4A4	2.95	.01	2.35	4.79	46.00		.14	1		2						

DDH: FAGA239

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													S.G. W.R.		
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAO %	HG %	MN %	AS %		BA %	
53.9	57.9	12842	4.0	2.7	4A4	2.95	.02	1.53	4.82	28.99		.27	1	1	2							
57.9	59.3	12843	1.4	1.3	4A4	3.04	.02	3.08	6.70	61.99		.27	3	1	4							
59.3	62.8	12844	3.5	2.4	4E4	4.26	.14	8.19	12.59	153.00		1.43	17	3	21							
62.8	64.0	12845	1.2	1.2	4A0	3.10	.02	.66	2.60	12.00		.20	2	5	8							
64.0	68.6	12846	4.6	1.9	4A4	3.10	.02	1.17	3.87	22.00		.40	2	3	5							

DDH: FAGA240

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAC %	HG %	MN %	AS %	BA %
48.0	49.4	12816	1.4	1.3	4A0	.04	.86	1.56	21.00											
49.4	51.8	12817	2.4	2.3	4E1	4.09	.09	4.00	7.80	70.00		.89	2	21	23					
51.8	53.3	12818	1.5	1.2	4A4	3.24	.08	4.13	7.80	56.00		.89	1	9	10					
53.3	55.0	12819	1.7	1.7	4A4	3.38	.09	5.70	10.10	81.00		.89	1	10	11					
55.0	56.5	12820	1.5	1.5	4A4	3.19	.04	1.82	4.05	36.00		.75	1	9	11					
56.5	58.2	12821	1.7	.9	4A4															
64.8	66.4	12822	1.6	1.6	4D5	3.11	.09	1.54	3.77	31.00		.41	2	7	9					
66.4	68.3	12823	1.9	1.7	4D5	3.14	.06	1.42	3.10	31.00		.48	1	8	10					
68.3	70.1	12824	1.8	1.7	4D5	3.13	.07	1.53	3.12	30.00		.27	3	6	9					
70.1	72.2	12825	2.1	2.1	4D5	3.06	.04	1.34	2.09	24.00		.41	2	4	6					
75.0	78.6	12826	3.6	1.7	4D5	3.00	.05	1.17	2.71	22.00		.62		4	5					
78.6	80.5	12827	1.9	1.8	4D5	3.19	.06	1.00	2.50	20.00		.34		3	4					
80.5	82.3	12828	1.8	1.8	4D5	2.87	.03	.93	2.11	16.00		.21			1					
82.3	84.1	12829	1.8	1.8	4D5	3.06	.06	1.54	3.83	39.00		.48	1	5	7					
84.1	86.3	12830	2.2	2.0	4D5	3.12	.04	1.25	3.22	27.00		.55	1	8	10					
86.3	87.8	12831	1.5	1.0	4D5	3.12	.06	1.23	2.94	28.00		.55	1	8	10					
87.8	89.6	12832	1.8	1.8	4D5	3.00	.04	1.48	3.42	29.00		.48	1	4	5					
90.7	92.4	12833	1.7	1.2	4D5	3.09	.03	1.20	3.73	29.00		.62	1	7	8					
92.4	93.9	12834	1.5	1.4	4D5	3.16	.03	1.55	4.98	33.00		.55	2	8	10					
93.9	95.0	12835	1.1	.9	4D5	3.35	.05	1.00	4.85	26.00		.55	2	12	15					
95.0	96.9	12836	1.9	1.9	4D45	3.83	.06	4.58	9.70	78.00		.96	2	17	20					
96.9	98.8	12837	1.9	1.7	4D45	3.82	.09	2.58	8.00	49.00		1.32	3	20	23					
98.8	100.3	12838	1.5	1.5	4D45	3.69	.08	3.18	7.50	52.00		1.23	2	18	21					
100.3	101.8	12839	1.5	1.5	4C5	3.76	.11	.73	2.58	22.00		1.78	3	22	25					
105.7	108.1	12840	2.4	2.3	4E4	3.88	.12	5.10	9.40	92.00		1.51	2	20	22					
108.1	110.0	12841	1.9	1.8	4A0	3.27	.13	1.11	2.89	31.00		.96	1	14	15					

DDH: FAGA241

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													S.G. W.R.
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAC %	HG %	MN %	AS %	
150.6	151.8	14697	1.2	1.2	3G91	.12	.09	.20	7.00											
151.8	152.9	14698	1.1	1.1	3G91	.08	.06	.08	3.00											
152.9	153.9	14699	1.0	1.0	4A4	3.09	2.16	4.01	34.00		.62	1	3	5						
157.0	157.9	14700	.9	.9	4E46	4.62	3.09	3.64	44.00		.62	2	12	15						
157.9	159.9	14701	2.0	2.0	4G4	4.68	8.00	8.20	98.00		.62	4	32	36						
159.9	161.8	14702	1.9	1.9	4E4*	4.73	7.20	8.10	100.00		.55	2	20	22						

DDH: FAGU002

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----															
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PC %	PY %	TOT FE	BAO %	HG %	MN %	AS %	BA %	S.G. W.R.	
.0	1.1	06242	1.1	.8	4D42	3.75	.08	4.74	8.16	79.00		1.23	1	17	.18							
1.1	3.0	06243	1.9	1.9	4A14	4.62	.05	3.15	5.90	59.00		1.37	2	19	.21							
3.0	3.9	06244	.9	.9	4D4	4.29	.02	5.09	8.48	83.00		.75	2	18	.20							
3.9	6.1	06245	2.2	2.1	4A14	3.48	.03	4.89	9.75	99.00		.89	1	10	.12							
6.1	7.4	06246	1.3	1.3	4A14	3.18	.02	1.72	5.90	42.00		.48	1	8	.10							
7.4	8.6	06247	1.2	1.1	4A14	3.28	.02	2.40	6.43	45.00		2.19	6	5	.12							
14.0	14.5	06248	.5	.5	4E4	4.48	.10	6.60	20.04	158.00		1.44	2	19	.21							











DDH: FAGU008

-----DEPTHS-----		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAO %	HG %	MN %	AS %	BA %	S.G. W.R.
24.8	27.0	06249	2.2	2.2	4A1	3.05	.05	.69	1.38	17.00		.41	2	5	7						
27.0	29.2	06250	2.2	1.7	4A1	3.55	.03	.65	1.28	15.00		.27	2	4	7						
29.2	31.2	06251	2.0	.9	4A1	3.18	.08	.99	2.00	24.00		.62	2	11	14						
31.2	33.4	06252	2.2	2.2	4L14	3.33	.04	1.79	3.07	26.00		.27	5	3	8						
33.4	35.5	06253	2.1	2.1	4L14	3.02	.03	2.04	3.25	31.00		.55	5	2	7						
35.5	36.5	06254	1.0	1.0	4A14	3.02	.05	3.46	6.90	58.00		.75	1	4	5						
36.5	38.7	06255	2.2	2.2	4L14	2.95	.04	1.70	4.36	37.00		.21	2	1	4						
38.7	40.8	06256	2.1	2.1	4L14	2.99	.04	1.99	3.98	38.00		.34	2	4	6						
40.8	42.3	06257	1.5	1.4	4E4	4.85	.16	7.10	13.67	112.00		1.10		29	30						
42.3	43.9	06258	1.6	1.6	4E4	4.11	.06	6.18	12.76	104.00		1.10	1	21	22						



DDH: FAGU010

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAO %	HG %	MN %	AS %	BA %	S.G. W.R.
1.0	2.3	06361	1.3	1.1	4D4	3.08	.03	3.90	8.80	86.00		.69	2	1	4						
2.3	3.9	06362	1.6	.9	4A14	2.97	.03	2.10	4.60	46.00		.69	1	1	3						
3.9	6.1	06363	2.2	1.8	4L14	3.05	.03	3.30	8.00	67.00		.75	1	2	3						
6.1	8.3	06364	2.2	2.0	4L14	3.09	.07	3.00	7.40	54.00		1.03	2	3	5						
8.3	10.3	06365	2.0	1.5	4L14	3.07	.08	3.90	5.10	71.00		.82	1	4	6						
10.3	12.2	06366	1.9	1.3	4LD4	3.37	.12	8.70	11.90	166.00		1.99	2	2	5						
12.2	12.8	06367	.6	.6	4L0	4.07	.02	.28	.22	5.00		.21	4	1	5						
12.8	14.4	06368	1.6	.9	5B19	3.20	.01	.88	2.90	14.00		.27	1		2						
14.4	16.1	06369	1.7	1.3	5B19	2.88	.01	.41	1.14	7.00		.14	3	1	4						
16.1	18.1	06370	2.0	1.2	4A1	2.97	.02	1.00	2.02	14.00	14.00	.14	4	2	6						
38.2	39.6	06371	1.4	.6	4L14	3.14	.01	2.40	4.60	35.00		.55	3	7	10						
40.8	42.9	06372	2.1	1.3	4A4	3.34	.05	5.10	7.70	83.00		.89	2	11	13						
42.9	44.4	06373	1.5	1.1	4L14	2.95	.03	2.90	5.80	49.00		.55	1	2	4						
50.4	52.5	06374	2.1	2.0	4L1	3.74	.04	.99	1.63	19.00		.27		6	7						
53.4	55.4	06375	2.0	2.0	4A14	3.28	.05	2.60	4.30	47.00		.62		7	8						
55.4	56.5	06376	1.1	1.1	4A14	3.17	.02	3.80	8.20	69.00		.55		6	7						
56.5	57.1	06377	.6	.6	4E12	4.13	.08	7.80	14.30	133.00		1.17	3	16	19						

DDH: FAGU011

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAC %	HG %	MN %	AS %	BA %	S.G. W.R.
.4	1.7	06510	1.3	.9	4D45	3.40	.06	3.67	9.42	76.00	70.00	1.10	1.13	14							
1.7	3.0	06511	1.3	.7	4D45	3.28	.01	2.87	6.23	47.00		.82	1.12	.13							
5.3	6.7	06512	1.4	1.4	4E*4	4.20	.06	3.98	17.60	83.00		.89	8.15	23							
6.7	8.0	06513	1.3	1.3	4E*4	4.48	.04	6.93	22.50	143.00		.82	8.15	23							
8.0	9.3	06514	1.3	1.2	4K4	4.03	.04	2.75	8.72	67.00		.41	4.20	24							

DDH: FAGU012

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														S.G. W.R.
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAC %	HG %	MN %	AS %	EA %	
15.8	17.4	06559	1.6	1.5	4E4	4.49	.11	5.63	11.10	90.00		.55	2	25	28						
17.4	19.1	06560	1.7	1.6	4E4	4.50	.14	4.57	6.96	86.00		1.92	1	29	30						
19.1	20.7	06561	1.6	1.6	4E4	4.58	.15	5.52	7.54	100.00		1.51		29	30						
20.7	22.3	06562	1.6	1.5	5C4*	3.19	.02	.60	3.37	21.00		.27	4	10	14						
22.3	23.6	06563	1.3	1.3	4E4	4.78	.15	4.49	6.53	84.00		.82	1	32	34						
23.6	25.0	06564	1.4	1.3	4E4	4.77	.20	5.41	10.50	95.00		1.65	1	28	29						
25.0	26.2	06565	1.2	1.2	4G4	4.63	.08	5.10	9.46	80.00		.96		13	14						
26.2	26.8	06566	.6	.5	4E4	4.70	.09	3.92	4.65	57.00		1.30		33	33						
26.8	27.3	06567	.5	.5	4G0	3.99	.01	1.36	3.70	23.00		.21		14	15						
27.3	28.8	06568	1.5	1.5	4E4	4.42	.09	3.57	5.98	68.00		.75		27	28						
55.1	56.4	06569	1.3	1.3	4D4	3.75	.51	6.59	5.70	133.00		2.40	5	15	21						
56.4	57.6	06570	1.2	1.2	4D4	3.80	.21	5.64	10.30	106.00	100.00	1.85	1	18	19						
57.6	58.7	06571	1.1	1.1	4E41	4.32	.15	6.01	10.90	90.00		1.99	1	24	26						
58.7	59.9	06572	1.2	1.2	4E41	4.14	.20	4.18	7.62	69.00		2.13	1	25	26						
59.9	61.0	06573	1.1	1.0	4C0	3.58	.35	.54	.81	16.00		1.65	2	22	24						
61.0	62.5	06574	1.5	1.3	4C5	4.50	.09	1.25	.91	31.00		1.78	1	18	20						
62.5	63.9	06575	1.4	1.2	4C5	4.03	.29	.12	.30	10.00		1.17	1	21	23						
63.9	65.5	06576	1.6	1.0	4D0	3.16	.26	2.61	3.71	56.00		2.26	2	21	24						
65.5	66.9	06577	1.4	.6	4D4	4.55	.13	5.15	6.36	78.00		1.65	1	17	19						
66.9	70.1	06578	3.2	1.2	4C0	3.92	.21	.48	1.35	18.00		.75	1	21	23						
70.1	73.0	06579	2.9	1.7	4C0	3.39	.18	.18	1.25	13.00		1.44	2	26	28						
73.0	74.9	06580	1.9	.8	4C0	3.73	.19	1.57	2.29	41.00	39.00	1.13	1	23	25						
74.9	75.9	06581	1.0	.5	4D*	3.49	.11	.27	7.78	12.00		1.30	8	14	22						
75.9	77.7	06582	1.8	1.8	4C0	3.25	.20	.36	2.40	20.00		.82	1	19	21						
77.7	79.8	06583	2.1	1.8	4C0	2.97	.21	.37	1.86	21.00		.34	1	18	19						

DDH: FAGU013

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														S.G. W.R.	
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAO %	HG %	MN %	AS %	BA %		
16.8	18.3	06423	1.5	1.5	4E4	4.21	.12	4.01	5.65	61.00			1.17	1	28	30						
18.3	19.4	06424	1.1	1.1	4E4\$	4.56	.15	6.14	1.26	117.00			1.58	2	24	26						
19.4	21.3	06425	1.9	1.9	4E4	4.62	.16	7.06	8.56	121.00			1.23	1	29	30						
21.3	23.1	06426	1.8	1.8	4E4	4.51	.15	3.79	4.53	70.00			.96		32	33						
23.1	24.9	06427	1.8	1.8	4E4	4.65	.16	4.06	6.04	61.00			1.57		33	34						
24.9	25.9	06428	1.0	.8	4G4\$	4.21	.14	4.95	7.57	99.00			1.23		24	25						
25.9	27.5	06429	1.6	.6	4E41	4.08	.04	10.30	18.20	141.00			.75	4	14	18						
55.4	57.2	06430	1.8	1.8	4D45	3.61	.16	5.67	8.46	89.00	86.00		.82	2	14	16						
57.2	59.5	06431	2.3	2.0	4D45	3.66	.28	4.30	6.11	73.00			1.65	2	19	22						
59.5	60.4	06432	.9	.6	4A0	2.92	.05	1.34	3.39	21.00			.27	2	2	5						
60.4	62.5	06433	2.1	1.5	4D5	3.59	.11	4.79	3.91	74.00			1.78	1	19	21						
62.5	64.4	06434	1.9	1.8	4C5	3.62	.26	.89	.69	18.00			1.37		24	25						
64.4	66.3	06435	1.9	1.9	4C5	3.53	.21	.93	.96	21.00			1.23	1	23	24						
66.3	68.6	06436	2.3	1.6	4C5	3.40	.19	.15	1.39	7.00			1.23	1	21	22						
68.6	71.6	06437	3.0	2.2	4D5	3.45	.18	2.76	3.28	42.00			1.65	1	19	20						
77.4	78.6	06438	1.2	.9	4E41		.16	11.30	18.30	162.00												
148.4	149.0	06439	.6	.6	4A0	2.83	.06	.42	.60	10.00			.55		5	6						
149.0	150.6	06440	1.6	1.6	4C0	3.79	.20	1.01	.86	20.00	21.00		.82	3	24	27						
150.6	152.5	06441	1.9	1.9	4A0	2.98	.08	.77	.84	10.00			.41	2	7	9						
152.5	153.9	06442	1.4	1.4	4C0	3.16	.06	1.35	1.36	15.00			.34	3	11	14						
153.9	157.2	06443	3.3	1.1	4A0	3.04	.03	.78	.81	9.00			.21	4	5	10						
157.2	158.6	06444	1.4	.8	4EL4	3.58	.06	2.59	2.63	30.00			1.10	9	14	24						
158.6	161.1	06445	2.5	2.5	4G8#	4.34	.23	4.04	3.67	49.00			2.06	11	21	32						
161.1	161.5	06446	.4	.4	4E47	4.29	.07	4.40	3.61	56.00			.89	10	24	35						
178.0	179.8	06447	1.8	1.8	4E8*	4.21	.22	1.56	.86	33.00			.75	9	24	34						
179.8	181.3	06448	1.5	1.5	4E8*	4.14	.15	2.66	.45	46.00			.75	11	21	32						
181.3	182.9	06449	1.6	1.6	4E8*	4.00	.20	1.36	.36	32.00			1.17	9	23	32						

DDH: FAGU014

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													S.G. W.R.		
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAC %	HG %	MN %	AS %		BA %	
19.4	21.2	06136	1.8	1.8	4ED4	4.52	.17	7.56	5.45	105.00		1.30	4	26	31							
21.2	21.9	06137	.7	.7	4C*	4.21	.35	.56	.50	33.00		2.26	4	23	28							
21.9	23.7	06138	1.8	1.8	4E*	4.46	.32	.35	.16	31.00		2.81	2	35	37							
23.7	24.9	06139	1.2	1.2	4G#4	4.35	.16	5.01	5.36	80.00		1.58	3	25	29							
25.5	26.5	06140	1.0	1.0	4E0	4.51	.38	.52	.36	35.00	30.00	1.03	1	38	39							
26.5	28.7	06141	2.2	2.2	4G84	4.59	.12	5.95	6.33	92.00		1.17	3	16	20							
28.7	29.5	06142	.8	.8	4G4	4.70	.06	10.17	7.42	150.00		1.10	1	20	22							
29.5	30.5	06143	1.0	.7	4C0	3.33	.12	1.44	1.74	22.00		.34	3	11	15							
30.5	32.3	06144	1.8	.8	4C0	3.86	.13	1.40	1.70	20.00		.62	14	19	34							
35.3	36.1	06145	.8	.8	4L2	3.37	.15	1.80	1.61	27.00		.21	9	8	18							
36.1	37.3	06146	1.2	1.2	4C8	3.42	.21	1.48	1.89	22.00		.41	4	16	20							
37.3	38.7	06147	1.4	1.4	4G48	4.65	.07	7.68	7.18	117.00		.41	2	7	9							
38.7	40.7	06148	2.0	2.0	4G48	4.57	.04	6.36	7.59	105.00		.27	2	6	8							
40.7	42.7	06149	2.0	2.0	4G48	4.58	.04	6.42	7.97	111.00		.27	1	4	5							
42.7	44.7	06150	2.0	2.0	4G48	4.58	.11	6.22	7.34	100.00	94.00	.34	1	11	13							
44.7	45.2	06151	.5	.5	4C6	3.86	.20	2.53	1.82	45.00		.69	8	23	31							

DDH: FAGU015

---DEPTHS---			SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													S.G. W.R.	
FROM	TO	CU %						PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAO %	HG %	MN %	AS %	BA %		
19.9	24.4	06919	4.5	1.3	4E4	4.54	.27	4.50	2.80	65.00			1.65	4	31	35						
24.4	26.7	06920	2.3	1.9	4E4	4.67	.23	3.00	2.70	64.00			1.44	3	35	38						
26.7	27.6	06921	.9	.7	4GE#	4.89	.14	6.50	6.20	86.00			1.51	4	21	26						
27.6	28.1	06922	.5	.4	4E48	4.86	.22	7.60	6.30	105.00			1.10	7	23	31						
28.1	29.1	06923	1.0	.9	4GE	4.67	.12	11.40	7.00	158.00			1.51	2	24	26						
29.1	30.5	06924	1.4	1.0	4L74	3.69	.25	3.00	2.80	39.00			.48	9	15	24						
67.1	67.9	06925	.8	.8	4D4	4.11	.13	5.30	8.10	97.00			.96	1	22	24						
67.9	68.6	06926	.7	.7	4L52	3.21	.07	.55	1.38	9.00			.34	5	8	14						
68.6	70.4	06927	1.8	.8	4G4	4.76	.19	7.10	10.90	130.00			.75	1	24	26						
70.4	71.2	06928	.8	.6	4D4	3.66	.13	6.60	9.10	134.00	125.00		1.03	1	31	33						
108.2	112.8	06929	4.6	1.7	4D43	3.98	.33	6.50	7.90	119.00			1.92	2	19	21						
112.8	114.0	06930	1.2	1.2	4E1	4.43	.33	1.65	2.60	43.00			1.58	1	34	36						
114.0	114.9	06931	.9	.6	4D4	3.82	.30	4.30	7.80	74.00			1.92	2	16	18						
114.9	116.9	06932	2.0	1.8	4E1	5.01	.40	2.20	2.80	43.00			2.26	1	34	36						
116.9	118.3	06933	1.4	1.3	4C0	4.54	.37	2.30	2.80	46.00			1.85	3	30	34						
118.3	120.0	06934	1.7	1.4	4D0	4.21	.42	3.00	6.40	56.00			1.78	3	25	28						
120.0	121.2	06935	1.2	1.2	4D53	3.80	.40	3.40	4.90	66.00			2.54	2	16	19						
121.2	123.6	06936	2.4	1.6	4C0	3.93	.27	1.60	1.57	30.00			1.44	1	25	27						
123.6	125.9	06937	2.3	1.8	4D0	3.99	.50	3.00	6.10	56.00			.75	1	22	24						
125.9	127.7	06938	1.8	1.6	4C0	3.53	.26	1.39	3.40	32.00	30.00		1.17	1	19	20						
171.7	172.2	06939	.5	.4	4K0	4.47	.15	.50	.53	23.00			1.10	4	34	38						
172.2	173.9	06940	1.7	1.4	4D*8	3.65	.07	2.80	2.90	39.00			.89	2	16	19						
173.9	175.7	06941	1.8	1.6	4D*8	3.94	.05	4.80	4.10	55.00			.89	4	19	23						
175.7	177.9	06942	2.2	2.0	4E86	4.38	.30	2.50	2.90	44.00			1.10	6	27	34						
177.9	179.8	06943	1.9	1.9	4D0	3.89	.34	2.90	3.20	41.00			.89	7	18	25						
179.8	181.4	06944	1.6	1.6	4D0	3.94	.22	3.00	2.80	41.00			.89	6	21	27						
181.4	182.9	06945	1.5	1.5	4LE	3.45	.13	3.00	2.10	38.00			.48	3	14	17						
182.9	184.0	06946	1.1	1.0	4LE	3.85	.14	2.50	2.10	42.00			.69	4	22	27						
184.0	184.8	06947	.8	.8	4A0	2.99	.08	.54	1.03	20.00			1.03	1	6	7						
184.8	185.9	06948	1.1	1.1	4GEL	3.71	.26	8.70	17.90	177.00	36.00		1.30	4	21	26						



DDH: FAGU017

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														S.G. W.R.
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAC %	HG %	MN %	AS %	BA %	
35.8	36.6	06752	.8	.8	4A14	3.27	.10	1.65	2.80	39.00			.89	1	14	15					
36.6	38.3	06753	1.7	1.4	4E4	4.65	.09	3.60	7.40	85.00			.82		34	35					
38.3	39.8	06754	1.5	1.4	4E4	4.66	.06	2.80	4.50	57.00			.89		38	39					
39.8	41.1	06755	1.3	1.3	4E46	4.76	.11	3.40	5.40	67.00			.62		37	38					
41.1	42.3	06756	1.2	1.2	4E46	4.58	.16	7.00	13.20	130.00			1.10		27	28					
42.3	43.3	06757	1.0	1.0	4D45	3.36	.15	4.00	7.20	76.00			.82	1	11	12					
43.3	44.1	06758	.8	.7	4G0	4.46	.06	4.00	7.60	91.00			.89		30	31					
44.1	44.6	06759	.5	.5	4K0	3.84	.04	.64	.98	40.00			.48	1	26	28					
44.6	45.0	06760	.4	.4	4E46	4.44	.11	4.90	10.40	98.00	88.00		.96		27	28					
45.0	45.5	06761	.5	.4	4K4	4.20	.02	2.40	6.20	51.00			.62		29	30					
45.5	46.3	06762	.8	.6	4E46	4.35	.05	4.10	8.10	87.00			.75	1	26	28					
46.3	47.3	06763	1.0	1.0	4G4	4.80	.14	3.40	6.80	96.00			1.03		20	20					
47.3	48.5	06764	1.2	1.0	4E4	4.87	.21	4.40	4.80	71.00			1.37		36	37					
48.5	50.9	06765	2.4	2.4	4G4	4.61	.14	7.40	14.00	131.00			1.51		23	24					
50.9	52.9	06766	2.0	2.0	4A0	3.31	.10	1.47	2.40	35.00			.82	1	13	14					
52.9	54.9	06767	2.0	2.0	4A4	3.44	.11	2.80	4.00	50.00			1.03		11	12					
54.9	56.5	06768	1.6	.2	4A0	3.17	.11	.61	1.20	18.00			.75		9	10					
68.2	69.8	06769	1.6	1.5	4A1		.06	.69	1.27	15.00											
69.8	71.3	06770	1.5	1.5	4A1		.06	.95	1.52	19.00											
73.4	74.7	06771	1.3	1.3	4L12		.06	.51	.95	12.00											
81.7	83.4	06772	1.7	1.6	4A1		.07	.08	.11	8.00											
93.7	95.4	06773	1.7	1.5	4A1		.12	.13	.51	7.00											
102.4	103.6	06774	1.2	1.1	4A1		.24	.07	.27	13.00											
108.0	108.5	06775	.5	.5	4E1		.51	.07	1.13	15.00											
108.5	110.4	06776	1.9	1.6	4A1		.08	.07	.51	9.00											
114.0	116.1	06777	2.1	2.1	4E1	4.55	.22	1.34	1.58	35.00			1.71	7	30	37					
117.7	118.3	06778	.6	.6	4D45	3.92	.07	5.70	11.50	91.00			2.06	1	17	19					
118.3	118.7	06779	.4	.4	4A41	3.39	.07	3.30	5.90	47.00			1.44	2	10	13					
118.7	119.2	06780	.5	.5	4L0	2.96	.02	.12	.57	6.00	2.00		.27	4	2	6					
119.2	119.9	06781	.7	.7	4D4	3.49	.05	3.40	7.60	52.00			.89	4	9	13					



DDH: FAGU019

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAO %	HG %	MN %	AS %	BA %
20.3	21.3	06114	1.0	.8	4E9*	4.59	.16	4.55	3.23	75.00		1.10	3	30	34					
21.3	22.9	06115	1.6	.8	4C*	3.79	.16	1.60	1.50	39.00		.27	12	13	26					
29.3	30.5	06116	1.2	1.2	4C0	3.47	.12	1.74	1.88	33.00		.21	6	10	16					
30.5	31.2	06117	.7	.7	4G*4	4.48	.25	4.24	5.38	78.00		.62	2	25	27					
31.2	33.4	06118	2.2	2.2	4E4	4.59	.13	2.33	1.69	47.00		.89	5	28	33					
33.4	34.8	06119	1.4	1.3	4E4	4.66	.13	5.39	5.11	91.00		.75	2	19	21					
34.8	36.6	06120	1.8	1.8	4G48	4.62	.15	6.60	6.42	114.00	106.00	1.70	5	20	25					
36.6	38.2	06121	1.6	1.4	4G4	4.33	.06	8.37	8.95	140.00		.41	2	8	11					
38.2	39.1	06122	.9	.9	4G2	4.01	.14	3.64	1.94	54.00		.48	12	15	27					
39.1	40.6	06123	1.5	1.4	4G2	4.26	.13	4.51	4.25	68.00		.41	5	22	27					
40.6	42.6	06124	2.0	2.0	4G4	4.57	.08	7.83	6.86	126.00		.41	2	6	8					
42.6	44.6	06125	2.0	2.0	4G4	4.69	.07	6.84	8.29	127.00		.34	3	8	11					
44.6	46.6	06126	2.0	1.9	4G4	4.48	.05	5.30	7.36	90.00		.41	3	10	13					
46.6	48.5	06127	1.9	1.9	4E48	3.82	.17	5.22	4.13	75.00		.41	10	22	32					
48.5	49.0	06128	.5	.5	4E48	3.65	1.04	2.60	2.07	39.00		.34	10	13	23					



DDH: FAGU021

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														S.G. W.R.	
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PC %	PY %	TOT FE	BAC %	HG %	MN %	AS %	BA %		
1.8	3.9	06178	2.1	2.1	4A14	3.01	.05	2.93	3.90	37.00			.89		4	5						
3.9	5.9	06179	2.0	2.0	4A14	3.19	.07	6.00	5.74	71.00			1.23	1	5	6						
5.9	7.9	06180	2.0	2.0	4A14	3.14	.07	5.35	6.93	64.00			1.03	1	3	4						
7.9	9.9	06181	2.0	2.0	4A14	3.14	.04	4.99	8.36	63.00			.96	1	3	4						
9.9	11.9	06182	2.0	2.0	4A14	3.14	.08	3.19	5.95	42.00			.96		3	4						
11.9	12.3	06183	.4	.4	4E24	4.18	.25	16.26	21.30	242.00			1.37	2	10	12						
12.3	13.5	06184	1.2	1.2	4D54	3.58	.07	7.53	11.94	114.00			1.37	1	10	11						
13.5	14.8	06185	1.3	1.3	4A4	3.24	.02	2.57	4.90	40.00			.82		10	11						
14.8	15.9	06186	1.1	1.1	4E4	4.00	.11	9.22	18.94	156.00	153.00		2.13	1	17	19						
36.4	38.0	06187	1.6	1.6	4L2	3.06	.03	.54	.80	6.00			.34	4	5	9						
38.0	39.6	06188	1.6	1.6	4L2	3.20	.06	.58	.55	7.00			.55	6	5	12						
39.6	41.8	06189	2.2	2.2	4G4	4.72	.12	7.56	6.88	105.00			.89	2	18	20						
41.8	43.0	06190	1.2	1.2	4E64	4.60	.12	11.21	5.98	113.00			.96	2	23	25						
43.0	44.5	06191	1.5	1.5	4L24	3.41	.16	1.99	1.33	24.00			.34	6	10	17						
44.5	45.5	06192	1.0	1.0	4G*4	4.14	.17	3.80	2.40	46.00			.41	10	21	32						
45.5	45.9	06193	.4	.4	4L14	3.28	.12	1.57	1.15	19.00			.21	5	9	14						







DDH: FAGU026

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														S.G. W.R.
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAC %	HG %	MN %	AS %	BA %	
.0	1.8	06391	1.8	1.5	4A3	3.69	.11	.55	.48	8.00		2.06	1	24	25						
1.8	2.8	06392	1.0	.9	5C4*	3.39	.05	.22	2.91	4.00		.89	4	14	18						
2.8	4.1	06393	1.3	1.3	4D0	3.65	.05	1.27	4.07	14.00		.69	3	20	23						
4.1	5.8	06394	1.7	1.7	4B4	2.96	.02	3.35	7.67	40.00		.27	1	1	3						
5.8	7.5	06395	1.7	1.7	4B0	2.76	.03	2.01	4.28	17.00		.21	1	1	2						
7.5	9.2	06396	1.7	1.7	4B0	2.85	.02	1.71	3.72	11.00		.14	1	1	2						
9.2	11.0	06397	1.8	1.8	4B0	2.88	.03	1.80	4.12	15.00		.27	1	1	3						
11.0	12.5	06398	1.5	1.5	4D4	3.00	.06	3.29	7.55	42.00		1.10	1	2	4						
12.5	13.9	06399	1.4	1.4	4B4	3.01	.04	3.54	8.22	40.00		.55	1	3	4						
13.9	15.4	06400	1.5	1.5	4B4	3.00	.06	3.27	7.95	42.00	52.00	.75	1	2	4						
15.4	17.4	06401	2.0	1.8	4B4	2.96	.03	3.44	6.82	37.00		.55	1	1	3						
17.4	19.4	06402	2.0	2.0	4B4	2.89	.03	1.82	5.36	10.00		.21	1	2	3						
19.4	21.4	06403	2.0	2.0	4B4	3.12	.09	3.55	7.00	41.00		1.23	1	6	7						
21.4	22.7	06404	1.3	1.2	4D0	3.16	.08	3.67	6.23	45.00		.96	1	7	9						
22.7	24.1	06405	1.4	1.4	4D0	3.10	.07	1.30	3.62	13.00		.34	1	8	9						
24.1	25.8	06406	1.7	1.7	4B0	2.93	.03	1.16	3.34	4.00		.21	1	2	3						
25.8	27.5	06407	1.7	1.7	4B0	2.83	.01	1.16	1.41	4.00		.14		1	2						
27.5	29.3	06408	1.8	.9	4B0	2.80	.07	2.26	1.93	23.00		1.17	1	3	4						
29.3	31.4	06409	2.1	1.9	4B4	3.00	.10	1.74	4.15	17.00		.41	1	2	3						
31.4	33.5	06410	2.1	2.1	4B4	2.96	.11	1.82	4.09	23.00	36.00	.62	1	4	5						
33.5	35.5	06411	2.0	1.7	4B0	2.94	.06	2.05	1.94	17.00		1.10	1	4	5						
35.5	37.0	06412	1.5	1.5	4L*	2.86	.03	.92	1.85	4.00		.21		2	3						
37.0	38.6	06413	1.6	1.6	4L1*	2.88	.07	1.09	2.14	5.00		.21	2	3	5						
38.6	40.0	06414	1.4	1.4	4L14	2.90	.04	2.83	4.30	51.00		.34	1	2	3						
48.1	49.7	06415	1.6	1.6	4A24	3.22	.07	3.57	8.56	58.00		.89	3	7	11						
49.7	50.3	06416	.6	.5	4L14	3.09	.03	3.46	8.05	58.00		.41	4	4	8						
50.3	52.4	06417	2.1	2.1	4A13	3.14	.02	3.22	8.37	60.00		.55	3	6	9						
52.4	54.1	06418	1.7	1.6	4A4	3.21	.04	3.72	6.43	49.00		.89	1	9	11						
54.1	55.9	06419	1.8	1.8	4A4	3.26	.08	4.66	9.00	66.00		.96	2	8	10						
55.9	57.1	06420	1.2	1.2	4B0	2.99	.04	1.22	4.14	58.00	21.00	.48	4	3	7						
57.1	58.2	06421	1.1	1.0	4B0		.05	1.43	1.35	22.00											
58.2	59.1	06422	.9	.3	4B0	3.47	.06	4.27	6.93	58.00		.82	1	13	14						







DDH: FAGU029

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													S.G. W.R.
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAC %	HG %	MN %	AS %	
22.6	25.4	08763	2.8	2.8	4DLO	.21	1.66	1.81	36.00											
55.7	56.4	08764	.7	.6	4E4	3.96	.17	4.80	8.10	76.00		.34	1	24	26					
56.4	57.7	08765	1.3	.6	4A0	2.91	.02	.57	1.56	13.00		.41	1	6	7					
57.7	59.8	08766	2.1	2.0	4E4	3.85	.09	7.40	14.80	117.00	117.00	.69		23	24					
59.8	62.0	08767	2.2	2.0	4A4	3.25	.06	3.80	9.50	65.00		1.03		10	11					
62.0	64.2	08768	2.2	2.0	4A4	3.16	.05	1.62	2.50	37.00		.89		12	13					
64.2	66.4	08769	2.2	2.2	4A4	2.87	.02	1.26	3.60	26.00		.48		2	3					
66.4	68.6	08770	2.2	2.2	4A4	2.81	.01	1.34	3.50	26.00		.41		2	3					





DDH: FAGU033

-----DEPTHS-----				-----ASSAYS-----																	
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PG %	PY %	TOT FE	BAG %	HG %	MN %	AS %	BA %	S.G. W.R.	
2.7	4.9	08780	2.2	2.0 4E0	3.16	.16	2.60	2.05	41.00		.69	3	12	16							
6.2	7.0	08781	.8	.8 4E7	4.34	.25	5.70	6.70	88.00		.34	12	14	26							
7.0	7.8	08782	.8	.8 4GE4	2.96	.07	7.00	10.20	107.00		.82	2	18	20							













DDH: FAGU040

---DEPTHS---			SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													S.G. W.R.
FROM	TO	CU %						PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAC %	HG %	MN %	AS %	BA %	
.0	2.0	08948	2.0	.9	4C0	2.99	.04	1.14	1.70	18.00		.41	3	5	8						
2.0	4.0	08949	2.0	.9	4C0	3.07	.08	1.76	1.74	29.00		.55		9	9						
4.0	5.8	08950	1.8	1.6	4C0	2.96	.06	1.01	.65	17.00		.41	2	4	6						
6.6	7.9	09104	1.3	1.3	4A0	2.95	.04	1.76	2.90	27.00		.62		4	5						
8.5	10.1	09105	1.6	1.4	4C0	2.92	.06	1.02	1.36	16.00		.41	1	6	8						
11.1	12.9	09106	1.8	1.8	4A0	2.89	.04	1.43	.65	16.00		.62		5	5						
17.7	18.6	09107	.9	.8	4A1	2.89	.03	1.59	2.50	19.00		.75		2	3						
18.6	20.5	09108	1.9	1.8	4A0	2.94	.03	1.44	1.84	17.00		.82		3	4						
21.5	23.5	09109	2.0	1.9	4A0	3.02	.05	2.50	2.03	28.00		.69		7	8						
23.5	25.5	09110	2.0	2.0	4A0	2.98	.07	2.60	.93	27.00		.82		6	6						
25.5	27.5	09111	2.0	2.0	4A0	2.98	.09	.33	.44	8.00		.82		8	8						
27.5	29.5	09112	2.0	1.8	4A0	2.93	.08	.27	.61	7.00		.69		7	8						
29.5	31.0	09113	1.5	1.5	4A0	3.06	.11	.13	.36	5.00		.48	1	10	12						
31.0	32.2	09114	1.2	1.2	4A0	2.96	.09	.08	.24	5.00		.27	2	7	9						
36.3	37.8	09115	1.5	1.5	4A0	3.10	.08	.29	1.00	8.00		.62		11	12						
37.8	39.5	09116	1.7	1.6	4A0	3.15	.09	1.47	2.70	25.00	27.00	.69		8	9						
39.5	41.5	09117	2.0	2.0	4A0	3.26	.08	2.60	3.00	50.00		1.10	1	11	12						
41.5	43.6	09118	2.1	2.1	4A0	3.28	.10	.09	.36	7.00		.82	1	16	17						
43.6	45.6	09119	2.0	2.0	4E4	4.43	.19	5.40	9.60	76.00		1.51	1	27	28						
45.6	46.6	09120	1.0	1.0	4G4	4.15	.19	5.50	8.10	97.00		1.37	1	23	25						
54.4	56.2	09121	1.8	1.8	4AG	3.65	.18	2.60	4.70	87.00		1.23	1	17	18						
57.9	59.9	09122	2.0	2.0	4GE*	4.06	.14	3.40	5.20	69.00		1.37	1	25	26						
59.9	61.9	09123	2.0	2.0	4GE*	3.97	.05	2.80	5.00	59.00		1.17	1	13	14						
61.9	63.5	09124	1.6	1.6	4GE*	4.43	.09	5.10	8.90	92.00		1.03		18	19						
64.6	65.6	09125	1.0	.9	4LE	3.59	.13	2.90	3.70	64.00	60.00	.75	1	15	17						
65.6	67.6	09126	2.0	1.9	4GE*	4.08	.10	3.40	6.10	63.00		.82	1	17	18						
67.6	69.6	09127	2.0	2.0	4GE*	4.29	.15	3.80	6.80	85.00		.96		20	21						
69.6	71.6	09128	2.0	2.0	4GE*	4.17	.26	3.50	6.30	105.00		1.30	1	23	24						
71.6	73.0	09129	1.4	1.4	4GE*	4.38	.21	4.70	7.80	114.00		1.17		20	21						
73.0	74.7	09130	1.7	.9	4GE*	4.33	.16	4.70	7.30	122.00		1.30		22	23						
85.8	87.8	09131	2.0	1.6	4A0	3.16	.11	.67	1.25	19.00		.55	7	9	16						
87.8	89.8	09132	2.0	1.7	4A0	2.98	.12	.16	.94	8.00		.34	5	6	11						
89.8	91.8	09133	2.0	2.0	4A0	3.02	.23	.26	2.00	15.00		.48	6	7	13						
91.8	93.8	09134	2.0	1.7	4A0	3.43	.33	1.69	3.10	44.00		.55	6	15	21						
93.8	95.8	09135	2.0	.9	4A0	3.28	.07	.47	2.30	16.00		.21	4	14	18						
95.8	97.8	09136	2.0	2.0	4A0	3.08	.11	.79	1.98	17.00		.14	2	9	12						
97.8	99.0	09137	1.2	1.2	4A0	2.93	.10	.09	.56	6.00		.21	3	6	10						
99.0	100.5	09138	1.5	1.5	4A0	3.03	.09	.16	.99	8.00		.41	4	7	11						
100.5	102.7	09139	2.2	2.2	4E4	3.84	.07	4.10	11.40	79.00		.89	5	17	22						
102.7	104.9	09140	2.2	1.8	4E4	3.76	.17	4.20	5.00	72.00		2.06	2	16	18						

DDH: FAGU041

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAC %	HG %	MN %	AS %	BA %
42.7	44.7	08933	2.0	1.1	4A1		.08	.38	.48	10.00										
44.7	46.7	08934	2.0	1.9	4A1		.07	.32	.64	11.00										
46.7	47.7	08935	1.0	1.0	4A1		.04	.40	1.23	8.00										
48.4	50.4	08936	2.0	1.5	4C0		.09	.47	.49	11.00										
50.4	52.8	08937	2.4	2.3	4C0		.08	.30	.38	8.00										
52.8	54.8	08938	2.0	2.0	4A1	2.84	.04	1.70	.67	29.00		.69	1	2	4					
54.8	56.8	08939	2.0	2.0	4A1	2.98	.04	1.86	3.60	24.00	26.00	.62	2	2	4					
56.8	58.8	08940	2.0	2.0	4A1	3.07	.14	.13	.39	10.00		.89	1	4	6					
58.8	60.8	08941	2.0	2.0	4A1	3.03	.04	1.70	1.00	23.00		.82	1	49	50					
60.8	62.0	08942	1.2	.7	4A14	2.96	.20	4.90	6.80	81.00		.62	1		1					
62.0	63.3	08943	1.3	1.3	4A14	3.10	.15	7.10	12.00	120.00		.96	1	8	9					
87.8	89.4	08944	1.6	1.6	4E4*	4.58	.03	1.66	3.60	23.00		1.30	1	35	37					
89.4	91.0	08945	1.6	1.5	4E4*	4.45	.05	2.80	4.50	36.00		1.65	1	30	31					
91.0	92.1	08946	1.1	1.1	4K4	4.10	.10	.29	.48	11.00		1.17	2	24	27					
92.1	93.5	08947	1.4	1.0	4A0	3.14	.11	.26	.47	10.00		.82	1	11	12					

DDH: FAGU042

						-----ASSAYS-----															
---DEPTHS---	SAMPLE	INT.	REC.	ROCK	S.G.	CU	PB	ZN	AG(AA)	AG(FA)	AU(FA)	PO	PY	TOT	BAC	HG	MN	AS	BA	S.G.	
FROM	NO.			UNIT	PULP	%	%	%	G/MT	G/MT	G/MT	%	%	FE	%	%	%	%	%	W.R.	
.0	2.7	08801	2.7	1.5	5C4	2.94	.03	.59	.66	12.00		.27	5	3	9						
2.7	4.8	08802	2.1	2.1	4CL	3.00	.03	1.11	2.08	21.00		.55	2	4	6						
4.8	7.3	08803	2.5	2.5	5C4	3.23	.03	.52	.55	11.00		.34	3	4	7						
7.3	9.8	08804	2.5	2.5	4A4	4.39	.05	4.80	5.10	64.00	63.00	1.37		6	7						
9.8	12.3	08805	2.5	2.5	4A4	3.20	.03	3.40	7.10	55.00		1.10	1	9	10						
12.3	14.9	08806	2.6	2.6	4A4	3.21	.06	5.00	7.60	76.00		1.17	1	7	8						
14.9	17.1	08807	2.2	2.0	4CL	2.89	.03	1.00	2.20	19.00		.34	1	4	5						
17.1	19.7	08808	2.6	2.6	4A3	3.01	.03	2.40	5.10	37.00		.62		6	7						
19.7	22.0	08809	2.3	2.3	4CL	2.94	.07	1.00	1.74	18.00		.55		6	7						
22.0	24.3	08810	2.3	2.3	4CL	2.92	.05	1.80	3.70	29.00		.41		3	4						
24.3	26.5	08811	2.2	2.2	4CL	2.96	.06	1.09	1.83	19.00		.55		7	8						
26.5	29.6	08812	3.1	3.1	4A0	3.16	.05	2.30	3.50	41.00		.89		12	12						
29.6	30.2	08813	.6	.6	4E4	3.73	.02	7.00	14.40	118.00		1.03	1	15	16						
30.2	32.9	08814	2.7	2.7	4E4	2.99	.06	5.50	11.90	97.00	94.00	.41		29	29						
32.9	33.8	08815	.9	.9	4E4	3.68	.09	9.00	17.70	164.00		1.44	2	4	6						

DDH: FAGU043

							-----ASSAYS-----														
---DEPTHS---	SAMPLE	INT.	REC.	ROCK	S.G.	CU	PB	ZN	AG(AA)	AG(FA)	AU(FA)	PO	PY	TOT	BAC	HG	MN	AS	BA	S.G.	
FROM	TO	NO.		UNIT	PULP	%	%	%	G/MT	G/MT	G/MT	%	%	FE	%	%	%	%	%	W.R.	
.0	3.0	07810	3.0	2.0	4CL	4.38	.04	9.90	17.60	177.00		1.03	1	18	20						
3.0	5.0	07811	2.0	1.9	4CL	2.93	.05	1.37	1.10	16.00		.34	2	4	7						
6.8	7.6	07812	.8	.8	4CL	2.89	.06	1.53	2.24	21.00		.41	1	3	4						
7.6	9.1	07813	1.5	1.5	4A4	2.97	.04	4.05	4.35	50.00		.89	1	3	5						
9.1	10.7	07814	1.6	1.6	4A4	2.86	.05	4.50	4.70	58.00	53.00	1.17	1	4	5						
10.7	12.7	07815	2.0	2.0	4A4	3.53	.01	4.32	9.10	77.00		1.03	1	14	15						
12.7	14.4	07816	1.7	1.7	4E14	2.89	.04	11.21	19.60	183.00		.34	1	3	5						
14.4	16.0	07817	1.6	1.6	4E14	4.64	.01	10.40	19.10	174.00		1.30	1	20	22						
16.0	17.7	07818	1.7	1.7	4E14	3.87	.01	9.50	17.40	178.00		1.44	1	11	13						
17.7	19.2	07819	1.5	1.5	4E4	4.66	.10	12.60	32.40	202.00		1.85	1	16	17						
19.2	20.7	07820	1.5	1.5	4E14	3.86	.01	8.40	14.60	144.00		1.44	1	12	14						
20.7	21.8	07821	1.1	1.1	4A34	3.46	.01	6.80	13.10	109.00		1.30	1	8	10						
21.8	23.3	07822	1.5	1.4	4E4	4.58	.08	7.50	14.20	136.00		1.51		27	28						
23.3	24.7	07823	1.4	1.4	4E4	4.45	.07	7.50	14.90	128.00		1.78	1	24	25						

DDH: FAGU044

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PC %	PY %	TOT FE	BAC %	HG %	MN %	AS %	BA %
.0	.9	08880	.9	.7	4L12	3.06	.07	.52	.65	11.00		.27	4	5	9					
.9	4.0	08881	3.1	3.1	4A0	3.04	.06	1.48	1.86	24.00		.75	1	8	9					
4.0	6.1	08882	2.1	2.1	4A14	2.98	.06	2.02	3.20	29.00	29.00	.41		4	5					
6.1	8.1	08883	2.0	1.8	4A14	3.15	.05	4.30	5.60	52.00		1.17	1	6	7					
8.1	10.2	08884	2.1	2.1	4A14	3.03	.04	3.80	6.90	47.00		.96	1	2	4					
10.2	12.2	08885	2.0	2.0	4A0	3.28	.05	1.56	3.20	32.00		.89	1	13	14					
12.2	13.4	08886	1.2	1.2	4A4	3.69	.08	6.30	8.90	100.00		1.58	1	14	16					
13.4	15.1	08887	1.7	1.6	4E4	4.45	.07	10.60	17.50	185.00		1.65	2	19	21					
15.1	16.8	08888	1.7	1.7	4E4	4.86	.09	7.30	14.80	114.00		1.44	1	31	32					
16.8	18.1	08889	1.3	1.2	4E0	4.78	.19	.95	.98	21.00		.96	1	45	46					
18.1	19.8	08890	1.7	1.5	4E4	4.25	.12	2.50	3.40	34.00		1.17	3	18	21					



DDH: FAGU046

						-----ASSAYS-----															
---DEPTHS---	SAMPLE	INT.	REC.	ROCK	S.G.	CU	PB	ZN	AG(AA)	AG(FA)	AU(FA)	PO	PY	TOT	BAC	HG	MN	AS	BA	S.G.	
FROM	TO	NO.		UNIT	PULP	%	%	%	G/MT	G/MT	G/MT	%	%	FE	%	%	%	%	%	W.R.	
.0	2.4	07974	2.4	1.7	4D453	3.35	.11	4.90	9.60	94.00		1.17	1	14	15						
2.4	4.0	07975	1.6	1.6	4D453	2.98	.06	2.01	2.70	35.00		.62	3	5	9						
4.0	5.2	07976	1.2	1.2	4D43	3.26	.10	4.40	7.30	81.00		1.17	1	12	13						
5.2	5.7	07977	.5	.5	5D4*	2.92	.03	.30	.85	9.00		.34	4	3	7						
5.7	7.4	07978	1.7	1.7	4D453	3.20	.05	5.00	9.10	81.00		1.17	2	8	10						
7.4	10.0	07979	2.6	2.6	5D4*	2.99	.04	1.02	4.10	19.00		.41	5	4	10						
10.0	10.5	07980	.5	.5	4D43	3.38	.01	6.10	10.60	98.00		.89	1	13	14						
10.5	11.2	07981	.7	.7	4A43	3.31	.03	4.40	9.50	76.00		1.03	1	13	15						
11.2	12.5	07982	1.3	1.3	4A13	3.55	.02	.59	3.80	15.00		.62	1	22	24						
14.3	14.7	07983	.4	.4	4E0		.02	.13	.21	3.00											
14.7	15.7	07984	1.0	1.0	4K4	3.51	.05	4.90	6.40	80.00		1.85	2	11	13						
15.7	17.4	07985	1.7	1.7	4A0		.02	.22	.29	10.00											
41.1	43.5	07986	2.4	2.1	4A43	3.34	.08	3.20	3.90	52.00	48.00	1.17	3	11	15						
43.5	45.4	07987	1.9	1.9	4A43	3.38	.10	4.30	3.80	73.00		1.51	1	17	18						
45.4	46.9	07988	1.5	1.5	4A43	3.31	.15	4.10	4.10	67.00		1.23	1	14	16						
60.7	61.9	07989	1.2	1.2	4EG4	4.26	.09	5.70	10.10	90.00		1.03	1	19	21						
61.9	62.4	07990	.5	.5	4D4	3.72	.04	8.40	13.70	124.00		1.23	1	18	20						
62.4	62.9	07991	.5	.5	4GE*	4.37	.15	7.10	11.90	117.00		1.71		22	23						
62.9	64.9	07992	2.0	2.0	4E4*6	4.50	.17	3.20	5.40	75.00		1.51		38	39						
64.9	66.8	07993	1.9	1.9	4GE	4.43	.10	4.80	9.20	77.00		1.30		19	20						
66.8	68.3	07994	1.5	1.5	4GE	4.30	.08	4.50	8.30	76.00		1.17	1	19	20						
68.3	69.8	07995	1.5	1.5	4GE	4.28	.05	4.20	8.30	71.00		1.03		11	12						
69.8	70.8	07996	1.0	1.0	4E4*6	4.80	.11	6.30	12.80	102.00	104.00	1.37	1	28	29						

DDH: FAGU047

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAC %	HG %	MN %	AS %	BA %
.0	2.4	07824	2.4	2.4	4D4	3.72	.20	7.30	8.70	119.00		1.30	2	15	17					
2.4	4.2	07825	1.8	1.8	4A4	3.63	.07	6.10	4.60	80.00		2.19	1	16	17					
4.2	5.0	07826	.8	.8	4D3	3.64	.12	2.80	1.71	31.00		1.30	2	21	23					
5.0	5.8	07827	.8	.7	5D4*	3.87	.07	3.50	3.10	47.00		1.03	2	22	25					
5.8	6.4	07828	.6	.6	4C0	2.96	.05	.21	.04	2.00		.41	3	2	6					
6.4	8.2	07829	1.8	1.8	5D4*	3.01	.03	.64	.90	9.00		.48	4	5	9					
8.2	10.7	07830	2.5	2.5	4A14	3.73	.08	3.70	2.25	42.00		1.51	1	21	22					
10.7	12.8	07831	2.1	2.1	4A14	3.64	.08	3.60	6.10	62.00		1.51	1	17	19					
12.8	15.0	07832	2.2	2.2	4A14	3.23	.02	3.00	4.70	53.00		1.23	2	10	13					
15.0	16.3	07833	1.3	1.3	4D4	3.51	.03	7.40	13.50	132.00	124.00	.82	2	12	15					
16.3	17.8	07834	1.5	1.5	4D4	3.80	.08	5.40	8.60	94.00		1.99	1	17	19					
17.8	19.7	07835	1.9	1.9	4G4#	4.42	.12	8.00	24.00	176.00		1.99	2	18	20					
19.7	21.0	07836	1.3	1.3	4D4	3.72	.02	7.50	16.90	107.00		.96	2	10	13					
21.0	22.2	07837	1.2	1.1	4G4#	4.42	.08	11.60	26.90	207.00		1.99	1	14	16					
30.3	32.2	07838	1.9	1.9	4AE4	3.65	.11	5.10	9.20	94.00		1.78	1	14	16					
32.2	33.7	07839	1.5	1.5	4K47	3.65	.08	4.10	9.00	81.00		.41	5	7	13					
33.7	34.4	07840	.7	.5	4D45	3.60	.05	4.70	8.60	83.00		2.13	1	12	14					
37.5	39.5	07841	2.0	1.8	4A0	3.74	.10	3.90	5.00	62.00		1.92	1	20	21					
57.5	59.4	07842	1.9	1.9	4EG4	4.47	.14	5.20	8.30	88.00		1.85	1	29	30					
59.4	61.2	07843	1.8	1.8	4EG4	3.99	.14	3.90	4.60	78.00	72.00	3.09	1	29	30					
61.2	62.9	07844	1.7	1.7	4EG4	4.70	.20	5.40	8.30	92.00		2.26		31	32					
62.9	64.8	07845	1.9	1.9	4EG4	4.50	.16	5.60	10.70	97.00		1.85		28	29					
64.8	65.4	07846	.6	.6	4A0	3.30	.09	1.56	2.60	24.00		.82		13	13					

DDH: FAGU048

---DEPTHS---			SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													S.G. W.R.
FROM	TO	CU %						PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAD %	HG %	MN %	AS %	BA %	
12.5	12.9	07901	.4	.4	5D4*	3.29	.07	.07	.38	9.00		.34	5	7	12						
12.9	14.7	07902	1.8	1.8	4E1	3.54	.06	2.60	5.10	44.00		.89	1	17	19						
22.3	24.4	07903	2.1	1.7	4D5	3.06	.04	2.60	6.20	56.00		.55	1	7	9						
24.4	25.9	07904	1.5	1.5	4D5	4.22	.06	5.10	12.00	115.00		.89	1	9	11						
25.9	27.2	07905	1.3	1.3	4D5	3.40	.09	3.70	7.80	69.00		.82	1	9	11						
28.8	31.1	07906	2.3	2.3	4L14	3.08	.04	2.30	6.50	33.00		.62	1	5	6						
32.1	33.2	07907	1.1	1.0	4LD	2.89	.01	1.34	3.80	26.00		.48		4	4						
33.2	35.3	07908	2.1	1.7	4LD	3.27	.02	4.30	8.20	72.00		1.10	1	10	11						
35.3	37.4	07909	2.1	2.0	4LD	3.32	.06	3.10	7.30	60.00		1.17	2	8	10						
37.4	38.0	07910	.6	.6	5D4*	3.03	.03	.37	2.40	13.00	10.00	.27	5	2	7						
38.0	39.6	07911	1.6	1.6	4D453	3.24	.03	4.80	10.10	77.00		1.17	1	13	15						
39.6	41.6	07912	2.0	2.0	4D453	3.72	.06	9.10	13.10	152.00		1.44	2	15	17						
41.6	43.6	07913	2.0	2.0	4D453	3.40	.11	5.30	13.10	83.00		1.51	3	10	14						
43.6	45.5	07914	1.9	1.9	4D453	3.40	.12	4.40	7.20	73.00		2.06	1	15	17						
45.5	48.0	07915	2.5	2.5	4A1	2.90	.07	.71	1.21	18.00		.62	1	5	6						
61.7	62.7	07916	1.0	1.0	4A0	3.08	.03	.51	1.83	8.00		.34	4	8	13						
62.7	64.5	07917	1.8	1.7	4A1	3.09	.03	.50	2.10	11.00		.34	1	11	12						
64.5	66.2	07918	1.7	1.7	4A1	3.14	.09	1.25	2.80	18.00		1.03	1	11	12						
66.2	67.1	07919	.9	.9	4H1	3.68	.15	.89	1.47	24.00		1.30	8	22	31						
67.1	68.2	07920	1.1	1.1	4H4	4.31	.24	7.20	14.80	157.00	159.00	1.03	8	18	26						
68.2	70.1	07921	1.9	1.9	4H1	3.80	.28	3.10	5.50	70.00		.89	17	16	34						
70.1	70.6	07922	.5	.5	4E46	4.20	.20	4.70	9.00	104.00		1.85	2	28	30						
70.6	71.8	07923	1.2	1.1	4A1	3.29	.16	6.40	8.70	120.00		.55	5	8	14						
71.8	72.8	07924	1.0	.7	4LH	3.50	.13	4.90	9.60	86.00		.69	3	13	17						
72.8	73.2	07925	.4	.4	10Q0	2.98	.04	.13	.20	6.00		.48		3	4						
73.2	73.6	07926	.4	.4	4J41	3.66	.06	10.20	18.90	180.00		2.33	4	11	16						
73.6	75.5	07927	1.9	1.9	4E46	4.11	.26	4.10	8.20	66.00		1.58	1	28	29						
75.5	77.3	07928	1.8	1.8	4E46	4.19	.22	5.70	11.50	124.00		1.58		27	28						
77.3	79.2	07929	1.9	1.9	4A1	3.35	.10	2.20	2.30	36.00	41.00	1.10		14	15						
79.2	80.6	07930	1.4	1.4	4A1	3.06	.10	.13	.06	11.00		.62		15	16						
80.6	81.8	07931	1.2	1.2	4A1	3.05	.06	.65	1.13	13.00		.69		13	14						
100.1	101.4	07932	1.3	1.3	4C0		.09	.69	.84	13.00											
101.4	103.1	07933	1.7	1.7	4A1		.09	.32	.58	9.00											
103.1	104.7	07934	1.6	1.6	4A1		.13	.15	.55	8.00											
.0	1.0	08694	1.0	1.0	4A4	3.59	.03	3.00	8.90	63.00		.96	1	16	18						
1.0	3.3	08695	2.3	2.3	4ED	3.95	.04	7.90	7.50	120.00		1.10	1	19	20						
3.3	4.2	08696	.9	.6	4E41	4.38	.10	7.80	3.90	90.00		1.51	2	27	29						
4.2	6.4	08697	2.2	2.2	4D0	3.75	.09	4.40	3.70	53.00		1.17	2	19	22						
6.4	8.3	08698	1.9	1.9	4D0	3.23	.05	2.50	4.90	40.00		.96	1	8	10						
8.3	10.5	08699	2.2	2.1	4A1	2.87	.03	1.33	2.90	20.00		.75			1						
10.5	12.5	08700	2.0	2.0	4A1	3.09	.06	2.10	3.20	40.00	42.00	.75	1	5	6						

DDH: FAGU049

-----DEPTHS-----		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAD %	HG %	MN %	AS %	BA %	S.G. W.R.
.0	2.8	08816	2.8	2.8	4C5	2.84	.03	1.42	3.20	24.00		.62		4	4						
2.8	5.6	08817	2.8	2.5	4C5	2.96	.03	1.64	3.70	29.00		.69		5	6						
5.6	8.4	08818	2.8	2.8	4C5	3.06	.08	2.10	3.90	38.00		.89	1	7	8						
8.4	11.2	08819	2.8	2.8	4C5	2.89	.02	.96	3.70	16.00		.48	1	3	4						
11.2	14.1	08820	2.9	2.9	4C5	2.91	.06	1.54	3.20	25.00		.48	1	3	4						
14.1	16.5	08821	2.4	2.4	4L14	3.00	.10	2.20	3.60	38.00		.75	1	4	5						
16.5	18.9	08822	2.4	2.4	4L14	2.95	.09	2.40	5.00	42.00		.62	1	3	4						
18.9	21.3	08823	2.4	2.1	4L14	3.00	.07	2.40	7.30	49.00		.62	1	2	4						
76.2	79.2	08824	3.0	3.0	4C5	2.84	.04	1.29	2.20	20.00	24.00	.48	1	2	3						
79.2	82.3	08825	3.1	3.1	4C5	2.91	.05	1.34	.35	10.00		.75		3	4						

DDH: FAGU051

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAO %	HG %	MN %	AS %	BA %	S.G. W.R.
.0	2.5	08733	2.5	2.2	4A4	3.33	.04	2.90	7.80	54.00		.75	2	11	14						
2.5	5.0	08734	2.5	2.5	4A4	3.41	.03	3.10	6.40	60.00		.96	1	15	17						
5.0	7.6	08735	2.6	2.4	4A4	3.46	.04	2.20	5.00	44.00		.82	1	15	16						
7.6	10.1	08736	2.5	1.6	4C5	2.92	.04	1.82	3.90	33.00		.62	1	3	5						
10.1	12.6	08737	2.5	1.6	4C5	3.01	.05	1.60	2.70	29.00		.96	1	7	8						
12.6	15.2	08738	2.6	1.1	4C5	2.96	.03	2.60	2.60	41.00		.96	1	4	6						
22.9	24.0	08739	1.1	.9	4A4	3.10	.03	3.50	5.70	71.00		.96	2	6	9						
24.0	27.4	08740	3.4	3.0	5D4	3.05	.04	1.20	4.70	23.00		.48	6	3	10						
27.4	29.2	08741	1.8	1.2	4A41	3.42	.03	1.78	4.30	30.00	33.00	.96	1	2	4						
29.2	29.9	08742	.7	.6	4L14	2.85	.03	1.34	4.20	25.00		1.85	1	2	3						
29.9	30.7	08743	.8	.8	5C4*	2.85	.01	.06	.12	2.00		.27	5	1	7						
30.7	31.9	08744	1.2	1.1	4L124	2.90	.05	1.09	1.84	18.00		.62		5	6						
31.9	33.8	08745	1.9	1.9	4L14	2.84	.05	.93	1.72	15.00		.69		4	4						
33.8	35.7	08746	1.9	1.9	4L14	2.88	.05	.74	1.18	15.00		.69		6	7						
35.7	38.2	08747	2.5	2.4	4A4	3.02	.08	2.50	4.70	45.00		.82		7	8						
38.2	40.7	08748	2.5	2.3	4A4	3.14	.05	1.71	3.10	33.00		.96	1	8	10						
40.7	41.7	08749	1.0	.8	4E4	4.04	.09	8.70	16.30	158.00		1.44	2	14	17						

DDH: FAGU052

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAO %	HG %	MN %	AS %	BA %	S.G. W.R.
.0	3.0	09168	3.0	2.4	4A14	3.38	.04	1.88	6.10	47.00		.89	2	14	17						
3.0	5.0	09169	2.0	2.0	4A14	3.33	.04	1.65	5.30	40.00		1.17	3	15	19						
5.0	7.0	09170	2.0	2.0	4A1 4	3.29	.05	2.40	5.50	46.00		.89	2	14	16						
7.0	8.7	09171	1.7	1.4	4A14	3.16	.03	2.02	5.20	36.00		.75	2	8	11						
8.7	10.6	09172	1.9	1.8	4A14	2.88	.05	1.74	4.20	64.00		.69	1	2	4						
10.6	13.7	09173	3.1	1.8	4A1	2.89	.04	1.89	2.60	35.00		.96	1	4	6						
13.7	16.2	09174	2.5	.9	4A14	2.95	.06	3.20	3.30	45.00		.82	1	5	7						
19.8	20.8	09175	1.0	1.0	4A4		.03	4.60	8.60	81.00											
25.9	27.5	09176	1.6	1.1	4A14	3.18	.09	2.40	4.40	43.00		1.10	2	9	11						
27.5	28.2	09177	.7	.7	4L14	3.03	.04	1.55	4.60	32.00	30.00	.75	2	4	6						
29.6	30.9	09178	1.3	1.3	4L14	3.01	.06	2.05	2.74	30.00		.41	2	3	6						
30.9	32.8	09179	1.9	1.8	4A1	2.97	.07	.93	1.31	15.00		1.17	1	7	9						
32.8	34.8	09180	2.0	2.0	4A1	2.99	.06	2.70	.96	23.00		1.30	1	4	5						
34.8	35.9	09181	1.1	1.1	4A14	3.01	.07	3.10	2.94	33.00		.75	1	6	7						
35.9	37.5	09182	1.6	1.6	4A0	3.10	.12	3.20	4.32	53.00		.89	2	8	10						
37.5	38.9	09183	1.4	1.4	4A0	3.41	.12	1.62	3.04	35.00		1.37	1	16	17						
38.9	39.4	09184	.5	.5	5C*	2.98	.03	.27	.30	5.00		.21	4	3	7						
39.4	40.5	09185	1.1	1.0	4AE	3.61	.15	5.50	9.60	100.00		1.17	4	13	17						

DDH: FAGU053

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAO %	HG %	MN %	AS %	BA %
.0	1.0	09030	1.0	1.0	4A34	3.68	.06	1.81	4.60	41.00		1.03	2	20	22					
1.8	3.0	09031	1.2	.6	4A134	3.78	.04	2.00	4.40	43.00	41.00	.65	3	10	13					
3.0	5.0	09032	2.0	1.4	4A134	3.34	.04	1.71	4.00	34.00		.89	2	13	16					
5.0	7.0	09033	2.0	2.0	4A134	3.56	.07	2.70	6.90	49.00		1.23	4	14	18					
7.0	9.1	09034	2.1	2.1	4A134	3.56	.07	1.86	5.80	43.00		1.17	3	16	19					
9.1	12.2	09035	3.1	2.0	4A14	2.96	.04	1.49	4.80	28.00		.55	1	2	4					
12.2	15.2	09036	3.0	2.6	4A14	2.99	.05	2.60	5.40	47.00		.69	1	2	4					
15.2	19.8	09037	4.6	1.2	4A14	2.98	.04	1.51	3.30	28.00		.55	2	4	6					
28.9	29.9	09038	1.0	1.0	4A13	3.41	.04	2.30	6.00	45.00		.82	3	12	15					
29.9	31.0	09039	1.1	1.1	4D0	3.27	.06	2.70	6.20	46.00		.48	4	8	12					
31.0	33.4	09040	2.4	.3	5C4*	3.21	.03	.48	.62	10.00		.34	8	3	12					
33.4	34.5	09041	1.1	1.0	4A14	3.24	.03	2.20	5.20	40.00	38.00	.96	3	19	22					
34.5	34.9	09042	.4	.4	5C4*	3.00	.03	.16	.68	8.00		.27	5	3	9					
34.9	36.0	09043	1.1	1.1	4L14	2.97	.06	1.93	2.50	30.00		.55	2	4	6					
36.0	37.7	09044	1.7	1.3	4A1	3.01	.05	2.30	1.45	29.00		.75	1	5	7					
37.7	39.0	09045	1.3	1.3	4A1	2.96	.06	1.40	2.70	20.00		.41	1	2	4					
39.0	41.1	09046	2.1	2.1	4A04	3.01	.04	2.30	4.60	38.00		.41	1	3	4					
41.1	42.6	09047	1.5	1.5	4A14	3.00	.03	1.85	4.70	35.00		.75	1	2	3					
42.6	44.6	09048	2.0	2.0	4A4	3.13	.05	2.20	4.60	36.00		.75	1	8	9					
44.6	45.7	09049	1.1	.9	4E4	4.01	.13	7.20	13.50	124.00		1.58	2	15	18					
1.0	1.8	09050	.8	.0	4L5	3.16	.05	.87	2.70	23.00		.48	3	8	12					

DDH: FAGU054

---DEPTHS---			SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													
FROM	TO	CU %						PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAC %	HG %	MN %	AS %	BA %	S.G. W.R.
.0	2.0	09585	2.0	1.5	4A4	3.45	.03	1.88	4.50	42.00		1.23	1	22	23						
2.0	4.0	09586	2.0	1.9	4A0	3.28	.02	1.50	3.10	33.00	33.00	1.03		10	11						
4.0	6.0	09587	2.0	1.7	4A4	3.11	.04	1.71	3.60	39.00		.69	1	13	14						
6.0	8.0	09588	2.0	1.6	4A4	3.27	.04	1.57	3.50	37.00		.82	1	17	18						
8.0	10.0	09589	2.0	2.0	4A4	3.29	.03	2.90	6.70	56.00		.89	1	14	15						
10.0	12.0	09590	2.0	2.0	4A4	3.48	.10	2.40	4.50	52.00		1.10	1	19	20						
12.0	15.2	09591	3.2	2.1	4A4	2.90	.04	2.20	3.60	29.00		.82	1	5	7						
15.2	16.8	09592	1.6	1.6	4A0	3.18	.05	1.67	3.00	33.00		.75		14	15						
16.8	18.2	09593	1.4	1.4	4A0	3.40	.08	1.02	1.62	25.00		1.10		17	18						
18.2	19.8	09594	1.6	1.6	4A4	3.31	.04	2.40	6.50	44.00		.96	1	12	13						
19.8	21.3	09595	1.5	1.5	4A4	3.39	.05	2.90	4.80	45.00		.89	1	15	16						
21.3	23.3	09596	2.0	1.9	4A4	3.48	.03	3.90	8.60	62.00	63.00	1.03	1	12	13						
23.3	25.3	09597	2.0	2.0	4A4	3.31	.03	4.50	9.00	73.00		.96	1	8	10						
25.3	27.3	09598	2.0	1.8	4A4	3.16	.04	3.20	8.00	55.00		.82	1	7	8						
27.3	29.3	09599	2.0	2.0	4A4	3.25	.13	3.90	9.40	69.00		1.30	1	9	10						
29.3	30.9	09600	1.6	1.6	4A4	3.49	.19	6.90	13.20	116.00		1.51	1	11	13						
30.9	32.5	09601	1.6	1.5	4A4	3.41	.05	6.20	13.50	106.00		1.23	1	8	10						
32.5	33.9	09602	1.4	1.4	4A4	3.28	.06	5.40	10.00	85.00		1.23	1	8	10						
33.9	34.9	09603	1.0	.9	4D0	3.01	.02	3.60	8.60	61.00		.62		4	5						
34.9	35.6	09604	.7	.7	4A4	3.41	.06	8.30	16.70	141.00		.89	2	7	10						
35.6	37.2	09605	1.6	1.6	4D0	3.07	.04	3.20	7.30	58.00		.82	2	6	9						
40.0	42.0	09606	2.0	1.2	4A4	3.39	.08	3.20	5.20	52.00	53.00	1.78	1	12	13						
42.0	44.3	09607	2.3	1.5	4C0	3.03	.10	.34	1.61	10.00		.89	2	9	12						
44.3	45.9	09608	1.6	1.6	4C0	2.99	.11	1.07	1.44	17.00		1.30		9	10						
45.9	47.2	09609	1.3	.8	4AE	3.38	.20	.82	1.25	18.00		1.78		20	21						
47.2	51.3	09610	4.1	1.6	4AE	3.49	.22	1.65	3.10	26.00		1.44	1	21	22						
51.3	53.3	09611	2.0	2.0	4A4	3.14	.04	3.40	7.90	48.00		.82	1	8	10						
53.3	55.4	09612	2.1	2.1	4A4	3.34	.05	2.80	5.10	46.00		.82	1	10	12						
55.4	56.1	09613	.7	.6	5D4*	3.01	.06	3.30	8.90	52.00		.27	8	1	10						
56.1	57.9	09614	1.8	1.8	4A14	2.99	.03	3.20	5.00	54.00		.55	1	2	4						
57.9	59.9	09615	2.0	.7	4A14	2.87	.03	2.70	3.50	40.00		.48	1	1	2						
59.9	61.9	09616	2.0	2.0	4A1	3.07	.05	1.93	1.21	24.00	27.00	1.51	2	5	8						
61.9	62.5	09617	.6	.6	4A1	2.99	.07	1.34	1.31	20.00		1.03	1	6	8						
62.5	63.4	09618	.9	.8	4L12	2.96	.03	1.75	2.60	21.00		.55	2	3	5						
63.4	65.4	09619	2.0	2.0	4A14	3.13	.02	2.80	5.40	39.00		.69	1	7	8						
65.4	67.1	09620	1.7	1.7	4A14	2.96	.01	3.50	6.10	44.00		1.37	1	5	7						
67.1	68.7	09621	1.6	1.6	4A14	2.93	.02	2.30	5.40	33.00		.62	1	4	5						
69.6	70.2	09622	.6	.6	4D0	3.06	.05	2.40	4.70	31.00		.55	3	6	10						
70.2	70.5	09623	.3	.3	5C4*	2.99	.01	.22	5.60	3.00		.27	10	1	11						
70.5	71.2	09624	.7	.7	4AE4	3.70	.14	4.50	6.90	77.00		1.58	2	14	16						
94.0	94.7	09625	.7	.7	4A14	3.25	.07	2.90	7.00	56.00		.48	4	7	12						
94.7	96.7	09626	2.0	1.8	4L124	3.05	.04	1.68	2.20	27.00	33.00	.75	4	5	9						
96.7	98.7	09627	2.0	2.0	4L124	3.10	.04	2.30	4.80	46.00		.89	3	5	9						
98.7	100.6	09628	1.9	1.9	4L124	2.95	.05	1.76	3.40	29.00		.39	3	4	7						
100.6	101.8	09629	1.2	1.2	4L124	2.93	.05	2.20	3.70	40.00		.55	3	6	9						
101.8	103.3	09630	1.5	1.5	4A14	3.12	.03	3.20	9.70	77.00		.48	5	3	8						
103.3	104.8	09631	1.5	1.5	4A14	3.41	.02	3.60	8.00	82.00		.41	6	6	12						
104.8	106.6	09632	1.8	1.8	4D0	3.14	.02	3.80	10.00	84.00		.41	5	3	9						
106.6	107.3	09633	.7	.7	5DC4*	3.14	.01	.56	5.90	14.00		.21	13	2	15						
107.3	109.1	09634	1.8	1.8	4A0	3.10	.03	.55	1.88	10.00		.27	9	5	14						
115.2	116.3	09635	1.1	1.1	4B0	3.01	.03	1.85	8.10	35.00		.27	5	5	11						

DDH: FAGU054

-----DEPTHS-----				-----ASSAYS-----																	
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAO %	HG %	MN %	AS %	BA %	S.G. W.R.	
116.3	117.0	09636	.7	.7	506	3.80	.04	1.37	2.80	20.00	29.00	.34	13	16	29						

DDH: FAGU056

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAC %	HG %	MN %	AS %	BA %
.0	3.1	08565	3.1	1.2	4LA1	2.71	.03	1.40	2.50	26.00		.55		6	6					
3.1	6.2	08566	3.1	3.1	4LA1	2.84	.06	.49	1.87	15.00	15.00	.55	1	6	7					
6.2	9.3	08567	3.1	3.1	4LA1	3.01	.04	1.25	4.00	25.00		.82	1	4	6					
9.3	12.3	08568	3.0	3.0	4LA1	3.08	.08	1.18	3.20	28.00		.62	1	7	8					
12.3	15.3	08569	3.0	3.0	4LA1	3.14	.02	1.25	3.80	28.00		.55	1	9	10					
15.3	18.3	08570	3.0	3.0	4LA1	3.14	.03	1.71	3.00	39.00		.69	1	9	10					
18.3	21.3	08571	3.0	2.1	4LA1	3.50	.05	1.97	3.70	31.00		.69	1	3	4					
21.3	24.3	08572	3.0	1.3	4A1	3.11	.04	1.09	2.20	23.00		.41	1	2	4					
45.4	47.7	08573	2.3	2.3	4A3	3.51	.07	1.23	2.30	26.00		.62	1	11	12					
47.7	50.1	08574	2.4	2.4	4A3	2.92	.05	.72	1.13	16.00		.48		7	8					
50.1	50.6	08575	.5	.5	4CL	2.86	.01	.19	.19	6.00		.21	5	1	6					
50.6	51.3	08576	.7	.5	5D4	2.84	.03	.14	.11	5.00		.27	4		5					
51.3	52.3	08577	1.0	1.0	4L14	3.23	.03	2.40	2.10	27.00	29.00	.48	1	1	3					
52.3	53.3	08578	1.0	1.0	4A14	3.06	.04	5.50	6.50	60.00		1.44	1	4	5					
53.3	55.5	08579	2.2	2.2	4A4	3.01	.04	3.30	6.50	42.00		.69	1	5	6					

DDH: FAGU057

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAC %	HG %	MN %	AS %	BA %
.0	1.8	08891	1.8	1.1	4D0	3.23	.03	1.92	3.90	41.00			.96		8	9				
1.8	3.8	08892	2.0	1.9	4A14	3.04	.03	1.74	3.50	35.00			.82		2	3				
3.8	5.8	08893	2.0	2.0	4A1	2.96	.03	.81	1.90	15.00			.69		5	6				
5.8	7.2	08894	1.4	1.2	4A1	2.96	.04	1.19	3.00	20.00			.96	1	2	4				
7.2	8.8	08895	1.6	1.6	4D0	3.18	.07	1.65	4.30	31.00			.82	1	8	9				
11.6	13.2	08896	1.6	1.2	4D0	3.02	.05	1.74	4.60	28.00			.48	2	2	4				
13.2	15.2	08897	2.0	1.7	4A1	2.99	.03	1.41	3.30	22.00			.48	1	1	2				
15.2	17.2	08898	2.0	2.0	4A1	3.00	.04	1.81	.55	35.00			.55	2	1	3				
17.2	19.2	08899	2.0	.8	4A14	2.96	.05	1.95	6.30	38.00			1.03	1		2				
19.2	21.4	08900	2.2	1.3	4A14	2.96	.03	1.85	3.40	30.00	36.00		.62	2	2	4				
21.4	22.8	09151	1.4	1.3	4D0	2.97	.08	3.40	5.70	52.00			.82	1	3	4				
22.8	24.7	09152	1.9	1.9	4A14	2.86	.03	2.60	5.20	39.00			.55	1	1	2				
24.7	26.7	09153	2.0	.7	4A14	2.81	.02	.63	3.40	12.00			.48			1				
26.7	28.7	09154	2.0	1.6	4A14	2.97	.05	3.60	7.10	60.00			.55	2	1	3				
28.7	30.3	09155	1.6	1.6	4A1	2.80	.01	.82	2.60	15.00			.34	1		1				
30.3	32.3	09156	2.0	1.5	4A14	2.96	.02	3.10	5.50	47.00			.48	1		2				
32.3	34.3	09157	2.0	2.0	4A1	2.81	.02	1.04	2.60	17.00			.41	1		1				
34.3	36.3	09158	2.0	2.0	4A1	2.86	.02	.92	1.52	15.00			.34	1	1	2				
36.3	38.3	09159	2.0	1.9	4A1	2.91	.02	1.05	1.76	15.00	18.00		.41	1	1	2				
38.3	40.3	09160	2.0	1.9	4A1	2.84	.02	.58	1.07	9.00			.55	1	1	3				
40.3	42.3	09161	2.0	2.0	4A1	2.79	.01	1.65	1.68	24.00			.41	1		2				
42.3	44.3	09162	2.0	2.0	4A1	2.88	.07	.54	.80	11.00			.75	1	5	6				
44.3	46.3	09163	2.0	1.5	4A1	2.94	.10	.66	.73	14.00			.34	1	7	8				
46.3	48.3	09164	2.0	2.0	4A1	2.86	.08	.52	.65	10.00			.27	1	5	6				
48.3	50.3	09165	2.0	.5	4A1	2.87	.10	.43	.53	9.00			.14	2	5	7				
50.3	52.3	09166	2.0	1.5	4A1	2.96	.12	.64	.57	14.00			.34	2	8	10				
52.3	53.3	09167	1.0	.7	4A1	3.01	.03	1.77	1.29	26.00			.55	1	3	5				

ODH: FAGU058

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAC %	HG %	MN %	AS %	BA %	S.G. W.R.
.0	2.1	06950	2.1	1.5	4E4	4.74	.26	2.70	3.10	41.00	43.00	1.85	1	37	38						
2.1	4.2	06951	2.1	2.1	4E4	4.92	.28	4.79	7.40	58.99		2.81	1	35	37						
4.2	5.9	06952	1.7	1.3	4G4	4.80	.27	6.40	9.30	105.00		1.98		21	22						
5.9	7.6	06953	1.7	1.5	4G4	4.67	.17	7.20	12.69	163.00		2.06		15	15						
7.6	9.0	06954	1.4	1.3	4E4	4.59	.07	7.49	12.40	99.00		1.16	1	27	29						
9.0	9.7	06955	.7	.5	5C*	2.93	.01	.17	.31	1.99		.20	6	1	8						
9.7	10.2	06956	.5	.5	4L0	3.37	.02	.66	1.05	6.99		.27	3	13	17						
10.2	11.7	06957	1.5	1.3	4E4	3.74	.07	1.77	3.29	36.00		.62	6	21	27						
11.7	13.0	06958	1.3	1.2	5A6	3.00	.05	.42	.58	3.00		.20	3	4	7						
13.0	13.7	06959	.7	.6	5C3	3.68	.16	3.89	7.09	80.00		.40	6	15	21						
13.7	14.7	06960	1.0	1.0	5B12	2.99	.04	.62	1.31	6.00	10.00	1.16	3	2	5						
14.7	15.7	06961	1.0	.8	4E4	4.83	.28	9.59	19.80	139.00		.34	2	20	23						
15.7	16.6	06962	.9	.8	4G4	4.55	.24	5.79	15.90	86.00		.47		16	17						
16.6	17.6	06963	1.0	1.0	4E4	4.59	.40	5.79	15.49	87.00		1.85	1	23	24						
17.6	18.5	06964	.9	.9	4E4	4.40	.17	7.40	18.00	119.99		1.98	1	24	25						
26.6	28.3	06965	1.7	1.5	4E10	3.20	.11	.76	.80	7.99		.20	8	12	20						
87.1	88.3	06966	1.2	1.1	4E84	4.42	.20	6.79	3.49	72.00		1.16	12	25	37						
88.3	89.4	06967	1.1	1.0	4E84	4.50	.20	7.99	3.39	97.00		1.78	6	28	35						
89.4	91.1	06968	1.7	1.4	4E0	4.46	.34	.55	.40	21.00		1.30	3	39	42						
91.1	92.7	06969	1.6	1.5	4E0	4.44	.31	.52	.64	19.00		1.23	2	38	40						
92.7	94.3	06970	1.6	1.2	4E4	4.32	.14	4.70	4.29	78.00		1.58	2	30	32						
94.3	96.3	06971	2.0	1.9	4E0	4.57	.20	1.87	1.11	47.00	48.00	1.64	1	36	37						
96.3	98.0	06972	1.7	1.7	4E4	4.08	.20	3.20	1.60	58.99		1.51	4	28	33						
98.0	98.6	06973	.6	.3	5D4\$	3.33	.14	.28	.17	13.99		.40	4	15	19						
98.6	99.8	06974	1.2	.9	4E4#	4.04	.08	5.92	7.20	92.00		.81	4	19	24						

DDH: FAGU059

---DEPTHS---			SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													S.G. W.R.
FROM	TO	CU %						PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAO %	HG %	MN %	AS %	BA %	
.0	2.0	07081	2.0	1.9	4A4	3.37	.05	4.50	11.09	74.00		1.37	1	10	12						
2.0	4.0	07082	2.0	2.0	4A4	3.37	.04	2.89	6.20	55.00		.81	1	15	16						
4.0	6.0	07083	2.0	2.0	4A4	3.22	.05	4.20	8.10	73.00		1.23	1	9	11						
6.0	7.8	07084	1.8	1.8	4A4	3.31	.05	3.70	8.19	68.00		1.37	1	12	14						
7.8	9.7	07085	1.9	1.9	4E14	3.45	.02	5.79	13.50	98.00		1.03	1	10	11						
9.7	10.6	07086	.9	.9	4D4	4.01	.10	9.50	16.89	165.00		1.64	1	7	9						
10.6	12.8	07087	2.2	2.2	4E14	3.81	.34	10.40	18.39	175.00	169.00	2.33	2	7	10						
12.8	14.9	07088	2.1	2.1	4E14	4.11	.14	9.19	18.39	158.00		2.06	1	11	13						
14.9	17.0	07089	2.1	2.1	4E14	4.54	.10	11.80	18.00	191.00		2.06	2	13	15						
17.0	18.8	07090	1.8	1.8	4E4	4.80	.20	6.40	6.99	92.00		1.70	1	33	35						
18.8	20.0	07091	1.2	1.2	4E4	4.65	.07	11.00	18.60	167.00		1.91	2	22	24						
20.0	21.1	07092	1.1	1.1	4E4	4.54	.08	10.00	17.19	156.00		2.06	2	22	24						
21.1	23.1	07093	2.0	2.0	4G4	4.69	.10	6.29	10.00	110.00		1.37		17	17						
23.1	25.1	07094	2.0	2.0	4G4	4.71	.22	6.90	10.50	122.99		1.91		19	20						
25.1	27.1	07095	2.0	2.0	4G4	4.70	.22	6.79	11.00	111.99		2.12	2	21	24						
27.1	29.1	07096	2.0	2.0	4G4	4.61	.23	6.50	10.50	133.00		1.91		19	20						
29.1	31.1	07097	2.0	2.0	4G4	4.63	.16	8.30	12.50	143.00	144.00	1.51	1	21	23						
31.1	32.8	07098	1.7	1.4	4G4	4.71	.27	6.59	10.00	123.99		1.10		23	24						
32.8	33.8	07099	1.0	1.0	4E4	4.62	.17	9.59	15.90	150.00		1.16	2	13	16						
33.8	35.2	07100	1.4	1.4	4E4	4.88	.22	11.00	15.09	157.00		.81	1	22	24						
35.2	37.2	07201	2.0	2.0	4G4	3.54	.19	6.50	10.00	111.99		.47		19	20						
37.2	39.2	07202	2.0	2.0	4G4	4.50	.16	6.50	10.19	101.00		.47	1	21	22						
39.2	41.2	07203	2.0	2.0	4G4	4.62	.08	6.90	10.19	90.00		.47	1	19	20						
41.2	42.9	07204	1.7	1.4	4G4	4.71	.17	6.40	10.30	101.00		.68	1	21	23						
42.9	44.6	07205	1.7	1.7	4G4	4.61	.10	6.90	11.40	114.99		.95	1	17	19						
44.6	46.3	07206	1.7	1.7	4G4	4.49	.11	6.99	13.40	119.99		.55	3	23	26						
46.3	47.5	07207	1.2	1.2	4E64	4.76	.34	9.40	13.80	180.00		.27	2	25	28						
47.5	48.5	07208	1.0	.9	4E4	4.50	.20	8.40	20.69	138.00		.68	5	20	25						
48.5	50.4	07209	1.9	1.9	4E4	4.74	.27	7.70	13.59	108.00		.55	3	28	32						
50.4	52.0	07210	1.6	1.6	4E0	4.61	.28	1.16	.76	29.99		.55	3	40	43						
52.0	53.6	07211	1.6	1.6	4E0	4.54	.28	.46	.51	21.00		.68	2	40	43						
53.6	54.5	07212	.9	.9	4E4	4.34	.11	6.50	11.19	107.00		1.70	2	25	27						
101.9	102.9	07213	1.0	1.0	4A0	3.06	.05	1.26	2.50	23.00		.75	2	8	10						
102.9	104.5	07214	1.6	1.6	4E4	3.91	.20	2.50	2.79	38.00		.81	2	25	28						
104.5	105.1	07215	.6	.6	4C0	3.31	.20	1.64	2.02	26.00		.89	5	13	19						
105.1	107.3	07216	2.2	2.2	4A13	3.02	.13	.19	.45	6.00		.55	2	8	11						
107.3	109.5	07217	2.2	2.2	4A13	3.06	.17	.20	.41	7.99		1.16	2	9	12						
109.5	110.1	07218	.6	.6	4E0	4.04	.16	2.29	2.50	35.00	30.99	.75	5	22	28						

DDH: FAGU060

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														S.G. W.R.
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAO %	HG %	MN %	AS %	BA %	
1.1	2.7	07444	1.6	1.5	4A14	4.49	.04	3.20	4.09	35.00		.95	1	7	8						
2.7	4.3	07445	1.6	1.6	4A14	3.29	.05	2.89	5.00	33.00		1.10		6	7						
4.3	6.5	07446	2.2	2.2	4A14	3.12	.05	2.70	3.39	33.00		1.03	1	5	7						
6.5	8.6	07447	2.1	2.1	4A14	3.14	.04	3.20	3.70	40.00		1.23		7	7						
8.6	10.7	07448	2.1	2.1	4A10	2.91	.02	.53	1.94	12.00		.62	1	2	3						
10.7	12.2	07449	1.5	.8	4A14	3.08	.02	3.79	4.09	49.00		1.10		4	5						
12.2	14.4	07450	2.2	1.5	4A10	2.54	.04	1.17	.84	19.00		1.23		7	7						
14.4	16.6	07451	2.2	2.2	4A10	2.95	.05	1.13	1.30	22.00		1.37	1	6	7						
16.6	18.7	07452	2.1	2.1	4A10	3.12	.10	1.58	2.02	30.99		1.03	2	9	12						
18.7	20.8	07453	2.1	2.1	4A13	2.93	.08	1.08	1.20	24.00	23.00	.81		7	8						
20.8	22.8	07454	2.0	2.0	4A13	3.04	.08	.83	1.24	19.00		.95	1	10	11						
22.8	24.0	07455	1.2	1.2	4A14	3.35	.13	2.02	3.89	39.00		1.23	3	13	16						
24.0	25.8	07456	1.8	1.8	4A10	3.18	.11	1.58	2.02	27.99		1.23	1	12	13						
25.8	27.6	07457	1.8	1.8	4A14	3.04	.08	2.62	3.49	42.00		1.10	1	6	8						
27.6	28.1	07458	.5	.5	4A30	3.49	.19	.34	.63	15.99		.89	2	21	24						
28.1	29.2	07459	1.1	1.0	4E0	4.01	.34	.16	1.40	13.99		1.10	1	33	35						
29.2	29.9	07460	.7	.7	4E*4	4.20	.23	5.50	9.30	91.00		1.58	1	25	26						
29.9	31.5	07461	1.6	1.3	4A10	3.37	.17	.46	1.19	18.00		.95	2	19	21						
31.5	32.5	07462	1.0	.9	4E4	4.63	.14	9.00	9.09	143.00		1.98	1	29	30						
32.5	34.1	07463	1.6	1.6	4G4	4.59	.17	4.70	7.79	91.00	80.00	.89	1	20	21						
42.8	44.0	07464	1.2	1.2	4E64	4.53	.13	4.20	5.40	60.99		1.37	1	30	31						
56.4	56.8	07465	.4	.4	4G#4	4.00	.13	6.00	10.69	107.00		1.16	4	16	20						
59.4	60.7	07466	1.3	1.2	4E#4	4.01	.05	2.70	3.79	74.00		1.10		18	19						
60.7	62.0	07467	1.3	.5	4E#4	4.13	.04	6.09	10.69	102.00		.62	3	14	17						
96.0	97.0	07468	1.0	1.0	4A0	2.97	.07	1.19	2.50	23.00		.55	2	3	6						
105.5	106.1	07469	.6	.6	4D4	3.66	.11	8.59	13.50	152.00		1.98	4	7	12						
106.1	107.9	07470	1.8	1.8	4E4	4.38	.29	3.29	5.00	67.00		1.91	2	30	32						
107.9	109.7	07471	1.8	1.8	4E4	4.00	.36	4.29	7.40	82.00		1.78	3	20	24						
109.7	111.5	07472	1.8	1.8	4E0	4.04	.58	.85	2.50	30.99		1.43	3	27	30						
111.5	112.3	07473	.8	.8	4E14	3.56	.17	4.40	7.09	82.00	75.00	1.51	2	17	19						

DDH: FAGU061

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													S.G. W.R.	
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAC %	HG %	MN %	AS %		BA %
1.2	3.2	07415	2.0	1.9	4A14	3.52	.05	3.10	5.29	38.00		.81	1	7	8						
3.2	5.2	07416	2.0	2.0	4A14	3.10	.07	2.39	3.79	31.99		1.03		6	7						
5.2	7.2	07417	2.0	2.0	4A14	3.16	.05	3.60	5.20	48.00		.81		5	6						
7.2	9.2	07418	2.0	2.0	4A14	3.33	.05	3.79	5.09	61.99		.95	1	11	12						
9.2	11.3	07419	2.1	2.1	4A30	3.66	.17	.31	1.03	13.00		.75	1	23	25						
11.3	13.4	07420	2.1	2.1	4A30	3.72	.23	.65	.34	35.00		1.51	1	26	28						
13.4	15.5	07421	2.1	2.1	4A30	3.49	.11	.81	1.55	30.99		.81	1	21	22						
15.5	16.9	07422	1.4	1.4	4A14	3.08	.05	2.02	4.20	38.00		.68		5	6						
16.9	18.4	07423	1.5	1.5	4A13	3.45	.16	.46	.55	28.99		.68	1	21	22						
18.4	20.4	07424	2.0	1.8	4E0	3.72	.20	.14	.38	14.99		1.10	2	26	28						
20.4	22.4	07425	2.0	2.0	4E0	3.60	.19	.08	.32	11.00		.68	1	23	25						
22.4	24.3	07426	1.9	1.9	4E0	3.66	.33	.11	.29	13.00		.89	2	26	28						
24.3	25.1	07427	.8	.7	4E4	4.49	.20	8.30	10.00	141.00		1.64	2	25	28						
25.1	25.8	07428	.7	.7	4E14	3.81	.23	3.29	3.20	57.99		1.78	1	24	25						
25.8	27.4	07429	1.6	1.6	4E74	4.84	.14	9.69	7.09	147.00		1.43	4	28	33						
27.4	29.0	07430	1.6	1.6	4E74	4.84	.14	8.59	4.40	137.00		1.58	4	30	35						
29.0	30.0	07431	1.0	1.0	4E0		.34	.77	.34	27.99											
30.0	30.6	07432	.6	.6	4G4	4.83	.16	7.59	9.30	114.99		1.78	1	22	24						
30.6	32.8	07433	2.2	1.9	4E4	4.17	.20	5.90	7.79	100.00		1.78	1	23	25						
55.8	56.3	07434	.5	.5	4G4	4.20	.14	5.00	7.40	92.00		1.43	1	17	18						
59.9	60.9	07435	1.0	1.0	4G4	4.46	.17	6.79	10.69	136.00		2.06	1	11	13						
87.4	89.1	07436	1.7	1.7	4E1	4.38	.10	2.10	2.50	45.00		1.10	1	32	34						
89.1	90.8	07437	1.7	1.5	4E1	4.24	.16	2.20	2.50	37.00		1.16	1	29	31						
90.8	91.3	07438	.5	.5	5A\$	3.16	.16	1.13	1.14	24.00		.55	2	9	12						
91.3	91.7	07439	.4	.4	4A1	2.95	.02	1.12	2.29	23.00		.62	2	4	6						
91.7	92.8	07440	1.1	1.1	4H1	3.99	.11	.98	1.39	24.00		.68	2	31	34						
92.8	96.7	07441	3.9	3.9	4A1		.08	.56	.73	13.99											
112.2	113.7	07442	1.5	1.5	404	3.62	.10	6.90	14.49	114.99	108.00	1.43	4	11	15						
113.7	115.2	07443	1.5	1.5	404	3.54	.10	6.99	14.69	120.99		1.64	2	9	12						

DDH: FAGU062

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAO %	HG %	MN %	AS %	BA %	S.G. W.R.
.0	1.6	07219	1.6	1.5	4E4	4.13	.13	6.40	9.59	107.00		1.16	2	23	25						
1.6	3.2	07220	1.6	1.5	4E4	4.69	.17	4.59	4.59	78.00		1.16	1	36	38						
3.2	4.8	07221	1.6	1.6	4E4	4.70	.16	5.29	5.50	79.00		1.98	2	34	37						
4.8	6.0	07222	1.2	1.0	4L14	3.10	.02	1.15	1.91	23.00		3.76	1	10	11						
6.0	8.0	07223	2.0	1.9	4E4	4.71	.23	6.70	9.30	135.00		2.06	1	20	21						
8.0	9.8	07224	1.8	1.6	4G4	4.66	.23	5.20	9.19	121.99		1.98		20	21						
9.8	10.5	07225	.7	.7	4G4	4.73	.17	3.70	6.70	89.00		3.02	1	24	26						
10.5	12.0	07226	1.5	1.5	4E64	4.71	.23	6.20	12.09	110.99		1.64		20	21						
12.0	13.6	07227	1.6	1.5	4E4	4.69	.05	5.90	11.50	84.00	83.00	1.03	1	30	31						
90.4	92.3	07228	1.9	1.9	4E4	4.42	.20	5.00	8.19	110.99		1.30	1	25	27						
92.3	94.1	07229	1.8	1.4	4E4	4.69	.19	7.40	10.59	120.99		1.51		19	20						
94.1	95.5	07230	1.4	1.4	4E4	4.66	.22	4.40	7.70	107.00		1.64	1	29	30						
95.5	96.9	07231	1.4	1.4	4E4	4.61	.23	5.09	8.80	113.99		1.23	1	26	28						

DDH: FAGU063

-----DEPTHS-----		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														S.G. W.R.
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAG %	HG %	MN %	AS %	BA %	
.0	2.5	07693	2.5	2.5	4E4	4.79	.10	7.40	10.80	86.00		1.70	2	28	31						
2.5	4.5	07694	2.0	2.0	4G4	4.83	.23	5.90	8.69	135.00		2.74		25	25						
4.5	6.8	07695	2.3	1.5	4G4	4.78	.10	5.09	10.40	105.00		1.43		17	18						
6.8	9.1	07696	2.3	2.3	4E4	4.86	.13	7.40	11.59	101.00		1.98	1	27	29						
9.1	9.6	07697	.5	.5	4D45	3.87	.01	10.00	4.90	139.00		1.30	1	13	14						
9.6	11.2	07698	1.6	1.6	4E4	4.38	.08	4.40	20.19	67.00	68.00	1.16	1	26	28						
11.2	11.9	07699	.7	.4	5C3\$	3.27	.10	1.14	3.49	28.99		.95	2	9	12						
11.9	13.3	07700	1.4	1.4	5A9	2.98	.02	.19	1.94	3.99		.68	2	3	5						
13.3	14.7	07801	1.4	1.4	5A9		.01	.08	.78	.99											
39.6	41.1	07802	1.5	1.3	4E47	4.40	.27	6.00	4.20	57.99		.14	16	20	37						
41.1	42.6	07803	1.5	1.5	4E47	4.29	.33	5.90	3.89	59.99		.14	14	21	36						
56.7	58.0	07804	1.3	1.3	4G4#	4.38	.08	5.29	5.79	83.00		.55	3	13	16						
58.0	59.4	07805	1.4	1.4	4G0#	4.00	.24	2.70	2.79	41.00		.89	7	22	29						
59.4	59.8	07806	.4	.4	4L0	3.20	.08	.68	1.16	13.99		.34	3	8	11						
59.8	60.9	07807	1.1	1.1	4G48	4.42	.16	5.50	8.40	95.00		.47	3	10	13						
60.9	62.7	07808	1.8	1.7	4G48	4.57	.05	6.99	8.40	116.99		.34	1	6	7						
62.7	64.4	07809	1.7	1.5	4KEG	3.95	.02	12.90	12.09	211.00	203.00	.34	4	10	15						



DDH: FAGU065

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														S.G. W.R.
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAO %	HG %	MN %	AS %	BA %	
.0	3.8	07519	3.8	2.5	4E4	4.75	.23	5.59	10.69	96.00		2.25	2		3						
3.8	5.7	07520	1.9	1.9	4G4	4.79	.23	7.29	10.90	140.00		3.22		20	20						
5.7	7.6	07521	1.9	1.8	4G4	4.75	.14	5.90	9.59	124.99		2.12	1	26	27						
7.6	9.8	07522	2.2	1.6	4G4	4.69	.14	8.10	15.49	144.00		2.39		9	9						
9.8	12.4	07523	2.6	1.9	4E4	4.78	.11	8.08	15.19	133.00		1.85	1	29	30						
12.4	12.9	07524	.5	.4	4D4	3.70	.01	7.95	18.39	138.00		.81	1	10	11						
12.9	14.2	07525	1.3	1.3	4A4	3.12	.02	2.83	7.70	58.99		.75	1	6	7						
14.2	15.1	07526	.9	.9	4D4	3.22	.01	4.00	11.30	82.00		.68	1	6	7						
15.1	16.7	07527	1.6	1.6	4E4	3.77	.08	4.96	6.20	93.00		1.78	1	22	23						
16.7	19.0	07528	2.3	2.3	4E4	4.17	.07	10.69	17.89	177.00	170.00	1.16	1	19	21						
19.0	21.5	07529	2.5	1.5	4A0	3.12	.02	1.14	2.25	21.00		.27	4	5	9						
42.8	43.3	07530	.5	.5	4L24	3.06	.05	.55	.88	13.00		.34	4	5	9						
43.3	43.8	07531	.5	.5	4C0*	3.54	.13	1.74	2.24	28.99		.55	7	15	23						
43.8	45.6	07532	1.8	1.8	4G4	4.61	.10	12.40	10.09	161.00		.89	2	11	14						
45.6	47.6	07533	2.0	2.0	4E4	4.58	.05	14.40	9.59	178.00		1.03	2	24	26						
47.6	49.6	07534	2.0	1.9	4E4	4.29	.11	9.59	8.10	131.00		.95	4	23	27						
49.6	50.4	07535	.8	.8	4L24	3.56	.14	1.97	2.04	36.00		.68	4	18	23						

DDH: FAGU066

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														S.G. W.R.
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAC %	HG %	MN %	AS %	EA %	
.0	2.0	12083	2.0	1.6	4E42	4.34	.23	9.30	14.80	136.00		2.95	2	19	21						
2.0	3.4	12084	1.4	1.0	4E42	4.69	.17	7.20	17.00	98.00		1.70	3	24	27						
3.4	5.4	12085	2.0	2.0	4E4	4.91	.23	4.29	7.99	69.00		2.87	1	34	36						
5.4	7.3	12086	1.9	1.6	4E4	4.75	.20	6.59	10.90	76.00		2.19	1	30	32						
7.3	9.3	12087	2.0	2.0	4EG4	4.78	.20	6.20	9.40	120.99		2.33		19	20						
9.3	11.4	12088	2.1	1.7	4EG4	4.86	.16	5.70	9.90	116.99		2.19	1	21	23						
11.4	13.9	12089	2.5	2.0	4G4	4.75	.10	3.89	8.69	83.00		1.23		14	15						
13.9	15.9	12090	2.0	1.4	4EG4	4.75	.14	6.70	10.90	121.99	122.99	1.37		34	35						
15.9	16.7	12091	.8	.8	4AL0	3.27	.07	1.30	2.50	34.00		.47	1	11	12						
16.7	18.4	12092	1.7	.7	4EA4	3.58	.08	2.89	4.09	49.00		.55	2	15	18						
18.4	19.4	12093	1.0	.9	5D4a	3.08	.04	.38	.58	7.99		.34	5	5	10						
19.4	20.5	12094	1.1	.9	4E4	4.46	.10	9.00	12.69	125.99		1.10	1	21	23						
20.5	22.0	12095	1.5	1.5	4EG4	4.73	.11	8.40	17.50	116.99		1.43	1	22	24						
22.0	23.4	12096	1.4	1.3	4G4	4.86	.19	5.59	9.69	98.00		1.30	1	22	23						
23.4	25.9	12097	2.5	2.5	4E4	4.59	.20	6.79	19.39	109.00		1.23	2	23	25						
39.2	41.3	12098	2.1	1.5	4E4	4.50	.17	4.40	4.50	72.00		.68	3	30	33						
41.3	45.7	12099	4.4	4.2	4L2	3.45	.10	1.39	1.37	31.99		.68	5	12	18						
47.2	48.7	12100	1.5	1.1	4E8		.17	2.50	1.92	37.00											
71.6	72.6	12101	1.0	1.0	4E0	4.20	.29	2.00	.47	49.00	42.00	.27	4	20	24						
72.6	73.3	12102	.7	.5	4L0	3.10	.08	.53	.19	22.00		.20	1	8	9						
73.3	76.1	12103	2.8	2.0	4E4	4.38	.11	2.39	3.10	61.99		.55	2	30	32						
76.1	78.5	12104	2.4	2.3	4G4#	4.45	.11	5.70	6.20	105.00		.81	1	17	18						
78.5	80.7	12105	2.2	2.2	4G4	4.53	.05	6.00	8.10	91.00		1.16	1	7	9						
80.7	83.2	12106	2.5	2.0	4G4#	4.28	.13	6.79	7.09	116.99		.95	2	20	23						
83.2	85.5	12107	2.3	1.1	4LEG	3.39	.23	.99	.73	29.99		.62	4	13	18						
85.5	86.8	12108	1.3	1.3	4G0#	3.31	.11	3.89	3.89	95.00		.68	2	23	26						
86.8	87.5	12109	.7	.6	4L2	3.45	.20	1.89	.85	41.00		.47	3	16	19						
87.5	88.8	12110	1.3	1.3	4G4#	4.13	.10	6.20	6.50	80.00	78.00	.81	2	22	24						
88.8	89.5	12111	.7	.5	4L3	3.12	.75	.34	.46	39.00		.62	3	2	6						
89.5	91.3	12112	1.8	1.8	4G4	4.63	.05	5.70	8.69	100.00		.55	2	7	9						
91.3	93.1	12113	1.8	.4	4G4	4.63	.05	6.40	7.59	105.00		.55	1	7	9						
93.1	95.0	12114	1.9	1.9	5D4*	3.10	.08	.91	.84	23.00		.27	3	6	9						
95.0	98.7	12115	3.7	2.7	4GE4	4.61	.05	5.90	8.50	108.00		.34	1	8	10						

DDH: FAGU067

-----DEPTHS-----				-----ASSAYS-----																	
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAO %	HG %	MN %	AS %	BA %	S.G. W.R.	
.0	3.1	11474	3.1	2.0	4A0	3.10	.08	1.57	1.53	25.00		.81	1	9	10						
3.1	5.4	11475	2.3	2.0	4A0	3.10	.07	1.66	1.78	24.00		.89	1	8	10						
5.4	7.6	11476	2.2	2.0	4AE	3.04	.02	2.60	4.59	34.00		.75	1	6	7						
7.6	9.2	11477	1.6	1.1	4A14	3.12	.02	4.29	5.00	48.00		.81	1	15	17						
9.2	10.8	11478	1.6	1.6	4A14	2.95	.04	2.89	3.99	37.00		1.23	1	3	4						
10.8	12.1	11479	1.3	1.3	4E05	3.87	.02	.72	1.92	23.00		.81	1	28	29						
12.1	13.5	11480	1.4	1.4	4AE	4.26	.02	.47	1.85	14.99	12.00	.55	1	12	14						
13.5	15.5	11481	2.0	1.9	4A43	3.33	.05	2.08	3.20	45.00		1.23	1	13	15						
15.5	18.2	11482	2.7	2.7	4A43	3.56	.11	3.60	8.40	55.99		1.70	1	15	17						
18.2	20.2	11483	2.0	2.0	4E4	4.46	.14	9.69	14.49	140.00		2.74	2	24	27						
20.2	22.4	11484	2.2	2.2	4E4	4.86	.23	11.09	16.09	134.00		4.17	1	25	27						
22.4	24.4	11485	2.0	2.0	4G4	4.63	.08	3.60	8.19	75.00		1.03		14	15						
24.4	26.4	11486	2.0	1.9	4G4	4.63	.05	5.70	13.40	111.99		.95		13	14						
26.4	27.5	11487	1.1	1.1	4E4	4.17	.11	5.90	13.19	95.00		1.43	2	20	22						
27.5	29.5	11488	2.0	1.8	4E4	4.57	.11	3.20	19.50	45.00		1.16	1	27	29						
29.5	31.5	11489	2.0	1.8	4E4	4.55	.10	5.79	24.00	83.00		1.10	2	23	25						
31.5	33.5	11490	2.0	2.0	4E4	4.86	.08	5.70	22.00	85.00		.68	2	23	25						
33.5	35.4	11491	1.9	1.9	4EA4	4.34	.20	5.29	16.39	140.00		.47	2	22	24						

DDH: FAGU068

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														S.G. W.R.
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAO %	HG %	MN %	AS %	BA %	
.0	2.0	11734	2.0	2.0	4A0	3.06	.05	.46	.56	13.99		.81	10	11							
2.0	4.0	11735	2.0	2.0	4A0	3.14	.08	1.51	.89	26.00		1.30	12	13							
4.0	6.0	11736	2.0	2.0	4A0	3.02	.05	2.50	1.39	27.99		1.51	7	8							
6.0	7.3	11737	1.3	1.2	4A4	2.87	.01	2.79	3.70	27.99		.62	1	24	25						
7.3	9.3	11738	2.0	2.0	4A4	2.93	.02	1.95	4.70	28.99		1.16	1	3	5						
9.3	11.0	11739	1.7	1.7	4A4	3.39	.05	3.70	7.49	51.00		1.43	1	13	14						
11.0	13.0	11740	2.0	2.0	4E4	4.50	.13	8.90	17.30	131.00	126.99	1.85	2	23	25						
13.0	15.0	11741	2.0	2.0	4E4	4.75	.26	9.19	15.49	159.00		3.83	1	27	28						
15.0	17.0	11742	2.0	1.8	4E4	4.75	.17	8.50	16.30	149.00		1.03	2	25	27						
17.0	18.9	11743	1.9	1.9	4E4	4.57	.05	4.50	11.50	91.00		1.10	1	27	29						
18.9	21.1	11744	2.2	2.2	4E54	3.93	.08	4.50	7.09	78.00		1.37	1	23	24						
21.1	22.2	11745	1.1	1.1	4A42	3.49	.02	3.60	4.59	68.00		1.23	2	15	17						

DDH: FAGU069

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAC %	HG %	MN %	AS %	BA %	S.G. W.R.
.0	1.5	11759	1.5	1.1	4AL	3.00	.08	.49	.59	11.00		.75	2	7	10						
1.5	3.3	11760	1.8	1.2	4A0	3.00	.07	1.69	1.35	21.00		.89	1	7	9						
3.3	4.7	11761	1.4	1.2	4A4	3.10	.05	2.60	4.59	40.00		.75	1	7	8						
4.7	6.0	11762	1.3	1.2	4A43	3.37	.04	1.99	4.20	41.00		1.03	1	14	16						
6.0	8.0	11763	2.0	1.6	4A43	3.77	.14	3.99	7.70	70.00		2.06	1	20	21						
8.0	10.0	11764	2.0	2.0	4E4	4.46	.33	7.09	14.49	139.00		2.06	1	24	26						
10.0	11.4	11765	1.4	1.3	4E4	4.50	.26	6.79	13.99	130.00		2.12	1	27	28						
11.4	13.4	11766	2.0	2.0	4A4	3.14	.07	1.81	4.59	40.00		.68	1	10	11						
13.4	14.4	11767	1.0	.9	4A0	3.29	.14	.52	.75	15.99		1.10	1	16	17						
14.4	16.4	11768	2.0	2.0	4A41	3.22	.05	3.99	9.19	65.00		.95	1	8	9						
16.4	18.4	11769	2.0	2.0	4A41	3.31	.01	5.59	12.59	99.00		.68	1	6	8						
18.4	20.4	11770	2.0	1.8	4A41	3.20	.02	4.59	11.90	80.00	80.00	.62	1	5	7						
20.4	22.0	11771	1.6	1.5	4A41	3.18	.02	5.09	11.40	90.00		.81	1	5	7						
22.0	23.5	11772	1.5	1.3	4A41	3.83	.10	6.99	11.00	123.99		1.78	1	18	20						
23.5	25.0	11773	1.5	1.1	4E4	4.46	.13	6.40	10.50	118.99		1.64	1	26	27						
25.0	26.7	11774	1.7	.3	4E4	4.46	.19	7.09	14.40	156.00		1.70		19	20						
26.7	27.4	11775	.7	.6	4G4	4.42	.42	5.59	12.50	134.00		2.87		18	19						

DDH: FAGU070

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PC %	PY %	TOT FE	BAC %	HG %	MN %	AS %	BA %
.0	1.8	11746	1.8	.7	4A0	3.00	.02	.55	1.52	14.99		.55	3	6	10					
1.8	3.8	11747	2.0	1.4	4A0	3.06	.05	2.39	1.03	31.99		1.03		9	10					
3.8	6.6	11748	2.8	2.5	4A24	3.18	.02	2.39	3.70	38.00		1.10	1	11	12					
6.6	8.7	11749	2.1	2.0	4A42	3.64	.08	7.99	11.69	119.99		1.98	1	13	15					
8.7	10.8	11750	2.1	2.1	4A42	3.89	.05	7.99	13.59	123.99	117.99	1.98	1	17	19					
10.8	12.8	11751	2.0	1.6	4E4	4.54	.17	9.40	19.60	136.00		2.19	1	21	23					
12.8	14.8	11752	2.0	1.6	4E4	4.63	.20	10.00	17.60	131.00		2.19	1	25	26					
14.8	16.7	11753	1.9	1.7	4E4	4.46	.10	7.90	15.59	138.00		.81	1	25	26					
16.7	19.3	11754	2.6	1.9	5D4\$	2.95	.01	.29	1.71	9.00		1.10	6	3	9					
19.3	20.8	11755	1.5	1.1	4A42	3.37	.11	3.00	6.09	45.00		1.43	1	13	14					
20.8	22.2	11756	1.4	1.4	4A42	3.35	.05	4.09	7.29	66.00		1.58	1	12	13					
22.2	24.0	11757	1.8	1.5	4E4	3.79	.11	6.90	12.69	119.99		1.43	1	14	16					
24.0	25.2	11758	1.2	.5	4E4	4.01	.14	6.70	17.19	124.99		1.30	1	17	18					

DDH: FAGU071

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----												
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAC %	HG %	MN %	AS %
.0	.9	11587	.9	.5	4C1	3.08	.05	.41	.41	10.00		.47	9	10					
.9	1.3	11588	.4	.4	4L0	2.95	.01	.11	.13	5.00		.07	4	2	6				
1.3	3.1	11589	1.8	1.8	4A1	3.18	.08	1.90	1.12	31.99	34.00	1.23	11	11					
3.1	4.9	11590	1.8	1.7	4A14	3.14	.05	3.39	4.50	42.00		.81	6	7					
4.9	6.1	11591	1.2	.8	4A3	3.37	.02	1.14	2.70	23.00		.62	1	14	15				
6.1	7.9	11592	1.8	1.8	4A34	3.49	.05	2.10	4.90	44.00		1.78	1	16	17				
7.9	9.8	11593	1.9	1.4	4A34	3.39	.04	2.50	5.59	43.00		.81	1	14	15				
9.8	11.2	11594	1.4	1.3	4E4	4.59	.02	13.50	23.00	209.00		1.03	1	16	18				
11.2	12.6	11595	1.4	1.0	4E4	4.58	.14	9.80	19.60	166.00		1.10	2	23	25				
12.6	14.8	11596	2.2	2.1	4A34	3.24	.07	2.20	4.50	37.00		.81	1	14	15				
14.8	17.0	11597	2.2	2.2	4A34	3.16	.02	3.29	7.59	55.99		.47	1	10	11				
17.0	17.3	11598	.3	.3	4E4	3.79	.05	5.79	13.19	103.00		.62	1	20	21				
17.3	19.3	11599	2.0	1.8	4AE4	3.49	.05	2.79	5.79	53.00	53.00	.81	15	16					
19.3	21.3	11600	2.0	1.8	4AE4	3.33	.05	5.40	15.09	97.00		.68	1	10	11				
21.3	21.7	11601	.4	.4	4E4	3.89	.04	7.49	17.80	133.00		.62	1	17	19				
21.7	22.8	11602	1.1	.7	4EA4	3.31	.05	5.40	9.69	83.00		.89	1	9	10				
22.8	24.3	11603	1.5	1.2	4EA4	3.49	.11	7.90	12.40	125.99		1.43	1	11	12				
24.3	24.7	11604	.4	.3	4E84	4.29	.02	12.09	20.10	150.00		3.02	5	15	21				
24.7	26.2	11605	1.5	1.0	5A69	3.16	.02	1.86	3.70	35.00		.27	2	8	11				

DDH: FAGU072

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													S.G. W.R.	
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAC %	HG %	MN %	AS %		BA %
.0	2.0	11803	2.0	1.6	4A0	3.12	.10	2.20	1.30	29.99			.89	1	11	12					
2.0	4.0	11804	2.0	1.6	4A0	3.18	.11	1.85	.68	28.99			1.30	1	12	13					
4.0	6.0	11805	2.0	1.8	4A0	3.16	.11	3.00	.80	45.00			.81	1	11	12					
6.0	8.0	11806	2.0	2.0	4A0	3.12	.11	.99	.46	20.00			.81	1	11	12					
8.0	10.0	11807	2.0	1.9	4A0		.10	.90	.72	18.00											
10.0	11.7	11808	1.7	1.5	4A0		.10	.57	.91	10.00											
11.7	13.6	11809	1.9	1.6	4A0		.05	.33	.54	9.00											
13.6	15.8	11810	2.2	2.0	4ACL		.08	.23	.35	6.99											
15.8	17.3	11811	1.5	1.2	4A0		.11	.26	.55	6.99											
17.3	19.0	11812	1.7	1.6	4A10	3.08	.11	.84	1.78	20.00			.75	1	9	11					
19.0	20.5	11813	1.5	1.2	4A0	3.10	.08	1.72	1.99	26.00			1.10	1	10	11					
20.5	22.2	11814	1.7	1.5	4A4	4.04	.28	2.60	3.49	53.00			1.37	1	28	30					
22.2	24.3	11815	2.1	2.0	4AE	3.77	.20	.65	1.28	28.99			.89	1	26	27					
24.3	25.9	11816	1.6	1.1	4A34	3.00	.08	2.20	3.20	37.00			1.10	1	5	7					
25.9	27.9	11817	2.0	1.9	4A4	3.93	.23	2.02	3.10	41.00			1.30	1	27	28					
27.9	30.4	11818	2.5	2.3	4AE	3.81	.08	1.57	2.60	46.00	44.00		.81	1	19	21					
40.5	42.0	11819	1.5	1.4	4EC	3.41	.02	1.37	1.06	26.00			.27	5	14	19					
42.0	42.7	11820	.7	.5	4D0	3.95	.14	3.00	5.20	69.00			.81	1	21	23					
63.4	65.2	11821	1.8	1.6	4EA		.05	1.44	2.29	27.00											
104.7	106.0	11822	1.3	1.3	4E6A	4.25	.13	3.10	3.39	43.00			.55	1	27	29					
103.0	104.7	11823	1.7	1.7	4A03	3.49	.14	1.67	2.50	27.00			.81	2	17	19					
106.0	107.5	11824	1.5	1.4	4EA	3.12	.08	.69	.97	13.99			.75	3	10	14					
107.5	109.0	11825	1.5	1.3	4A13	3.08	.16	1.34	1.67	23.00			.68	3	7	11					
110.2	111.7	11826	1.5	1.4	4ES	4.11	.26	2.89	2.89	45.00			1.70	2	35	38					
109.0	110.2	11827	1.2	1.1	4A13	2.83	.02	.49	1.14	9.00			.27	1	1	3					
116.8	118.0	11828	1.2	1.2	4AEL	3.27	.08	.92	1.38	15.99			1.98	3	13	16					
114.2	116.8	11829	2.6	1.2	4A0	3.02	.10	.76	1.70	13.00			.20	1	8	9					
118.0	120.0	11830	2.0	2.0	4A0	2.99	.05	.90	1.52	21.00	19.00		.47	1	7	8					
122.0	123.6	11831	1.6	1.6	4EAH	3.95	.07	1.47	1.71	36.00			1.37	10	24	34					
120.0	122.0	11832	2.0	1.2	4A0	2.91	.02	.99	1.68	19.00			.55	2	4	6					
124.6	126.6	11833	2.0	2.0	4D45	3.50	.16	7.20	12.69	125.99			2.19	2	10	12					
123.6	124.6	11834	1.0	.8	4A4	2.85	.05	2.50	.70	5.00			2.60	1	3	5					
126.6	128.6	11835	2.0	2.0	4D45	3.56	.02	9.00	19.60	159.00			2.81	2	7	9					
128.6	131.0	11836	2.4	2.4	4D4	3.54	.10	7.29	15.69	114.99			1.85	2	7	9					
131.0	132.9	11837	1.9	1.9	4A30	3.77	.02	1.44	3.10	38.00			1.85		23	24					
132.9	134.1	11838	1.2	1.2	4EG	4.02	.04	2.29	5.50	54.00			.27		27	27					
134.1	135.6	11839	1.5	1.3	4D45	3.58	.11	8.80	14.19	141.00			1.43	2	9	11					
135.6	137.1	11840	1.5	1.5	4D45	3.62	.04	10.00	14.49	156.00	162.00		1.70	2	8	10					









DDH: FAGU079

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														S.G. W.R.
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAO %	HG %	MN %	AS %	BA %	
.0	2.5	11841	2.5	2.0	4A0	3.18	.08	1.30	.91	21.00		.81	11	12							
2.5	4.9	11842	2.4	2.2	4A0	2.99	.05	.46	.23	11.00		1.64	5	6							
4.9	6.4	11843	1.5	1.4	4A4	3.04	.04	3.70	3.20	44.00		1.51	5	5							
6.4	7.8	11844	1.4	1.4	4A4		.02	3.16	2.60	34.00											
7.8	9.8	11845	2.0	2.0	4A4	3.06	.02	2.70	2.39	30.99		2.19	5	5							
9.8	11.8	11846	2.0	2.0	4A0	2.95	.02	3.10	1.05	30.99		2.74	4	5							
11.8	13.8	11847	2.0	2.0	4A0	3.18	.04	2.39	.65	27.99		1.51	1	13	14						
13.8	15.4	11848	1.6	1.6	4A0	3.08	.05	.94	.41	27.00		.40	1	11	12						
15.4	16.7	11849	1.3	1.3	4A0	3.31	.10	.90	.52	19.00		1.70	1	13	14						
16.7	18.2	11850	1.5	1.5	4A4	3.12	.11	3.29	5.70	41.00	30.99	1.16	1	10	12						
18.2	19.7	11851	1.5	1.5	4A0	3.16	.08	2.60	1.37	33.00		1.30	11	12							
19.7	21.7	11852	2.0	2.0	4A4	3.18	.14	3.79	5.29	51.00		1.98	1	10	12						
21.7	23.0	11853	1.3	1.3	4A0	3.00	.07	1.65	.45	25.00		1.30	7	8							
23.0	25.0	11854	2.0	1.9	4A4	3.06	.08	3.89	4.29	50.00		1.03	1	5	6						
25.0	27.0	11855	2.0	2.0	4A4	3.22	.08	2.50	3.60	40.00		1.10	11	12							
27.0	29.1	11856	2.1	2.1	4A4	2.91	.16	5.09	5.00	96.00		2.19	1	18	19						
29.1	31.2	11857	2.1	2.1	4A4	3.56	.14	3.70	4.29	70.00		1.91	1	18	19						
31.2	33.2	11858	2.0	1.7	4E4	4.29	.22	1.83	3.20	34.00		1.51	1	34	36						
33.2	35.2	11859	2.0	1.9	4E4	4.61	.31	3.79	5.00	63.99		1.64	1	35	37						
35.2	36.5	11860	1.3	.8	4E4	4.67	.28	4.29	10.00	97.00	93.00	2.19	2	28	31						
64.7	66.6	11861	1.9	1.9	4H2	3.64	.08	4.50	7.70	65.00		.27	11	10	21						
66.6	68.6	11862	2.0	2.0	4EH	4.06	.23	6.29	11.09	100.00		.47	9	17	27						
68.6	70.6	11863	2.0	2.0	4E4	4.63	.24	8.80	12.50	145.00		.62	3	26	29						
70.6	72.6	11864	2.0	2.0	4E4	4.34	.14	5.40	7.99	106.00		.75	1	23	25						
72.6	74.6	11865	2.0	2.0	4E46	4.54	.26	4.90	8.10	116.99		1.85	22	23							
74.6	76.6	11866	2.0	1.9	4E4	4.50	.20	4.59	6.70	112.99		1.85	26	27							
76.6	78.4	11867	1.8	1.8	4EG4	4.42	.14	5.79	9.80	126.99		2.81	1	24	25						
78.4	80.1	11868	1.7	1.6	4D7	3.20	.08	1.97	3.20	39.00		.47	3	7	11						

DDH: FAGU081

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAO %	HG %	MN %	AS %	BA %	S.G. W.R.
9.1	9.7	07682	.6	.5	4A4	3.33	.05	3.99	3.49	55.99		1.10	4	9	14						
9.7	10.0	07683	.3	.3	4L0	3.00	.02	.38	.49	6.99		.34	2	3	5						
10.0	11.0	07684	1.0	1.0	4D4	3.02	.02	4.40	7.29	68.00	70.00	.81	1	2	3						
11.0	12.7	07685	1.7	1.7	4D4	3.06	.07	4.79	5.90	79.00		1.16	1	4	5						
12.7	15.0	07686	2.3	2.2	4A14	3.04	.07	3.60	3.29	52.00		1.10		4	5						
15.0	16.8	07687	1.8	1.8	4L1	2.89	.02	.96	.57	11.00		.81		2	2						
16.8	18.8	07688	2.0	2.0	4L1	2.95	.02	1.65	1.53	21.00		.47	1	1	2						
18.8	20.8	07689	2.0	1.9	4L1	2.95	.02	1.90	1.16	26.00		.62	1	2	3						
20.8	22.8	07690	2.0	2.0	4L1	2.93	.02	1.32	.69	19.00		.55	1	1	2						
22.8	24.8	07691	2.0	1.8	4L1	2.98	.02	1.76	.84	26.00		1.37	1	3	4						
24.8	26.4	07692	1.6	1.6	4L1	2.93	.01	2.70	2.39	34.00		.62	1	1	2						

DDH: FAGU083

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													S.G. W.R.		
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT. FE	BAC %	HG %	MN %	AS %		BA %	
5.7	7.6	06799	1.9	1.5	4A41	3.14	.02	3.50	7.09	65.00		.68	4	4	8							
7.6	8.3	06800	.7	.7	4A10	3.12	.10	1.30	3.00	25.00	21.00	.81	3	10	14							
8.3	9.9	06901	1.6	1.1	5C4*	2.99	.02	.35	.56	11.00		.27	2	6	9							
9.9	11.3	06902	1.4	1.4	4A1	3.00	.05	1.25	1.93	24.00		.40	3	5	8							
11.3	13.7	06903	2.4	1.8	4L1	2.91	.05	.79	1.49	19.00		.40	2	4	6							
13.7	15.5	06904	1.8	.4	4L1	3.04	.07	1.16	2.70	25.00		.27	1	8	9							
15.5	16.6	06905	1.1	1.1	4A4	3.25	.01	3.20	6.79	58.99		.55	1	10	11							
16.6	17.8	06906	1.2	1.1	4ED	3.08	.02	7.29	1.47	120.99		.89	1	22	23							
17.8	20.5	06907	2.7	1.8	4A4	3.35	.01	4.09	9.69	89.00		.89	1	9	11							
20.5	23.5	06908	3.0	1.7	4E4	3.70	.05	3.99	13.30	122.99		.81	2	11	14							



DDH: FAGU085

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														S.G. W.R.
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAC %	HG %	MN %	AS %	BA %	
8.9	10.7	06909	1.8	1.8	4A0	3.35	.16	.69	1.23	20.00		1.16	3	15	18						
10.7	12.2	06910	1.5	1.5	4A0	3.16	.08	.80	1.99	19.00	17.00	.47	3	6	9						
12.2	13.9	06911	1.7	1.3	4A0	2.97	.08	.64	1.37	15.99		.20	2	5	8						
13.9	14.4	06912	.5	.3	4A14	3.16	.05	2.60	6.70	44.00		.55	3	6	9						
14.4	15.2	06913	.8	.8	4E4	4.61	.01	.40	9.00	79.00		.81	1	33	34						
15.2	17.0	06914	1.8	1.8	4E4	4.67	.14	6.90	7.79	126.99		.81	1	26	28						
17.0	19.1	06915	2.1	1.5	4E4	4.70	.13	7.70	20.80	142.00		.95	1	25	26						
19.1	21.0	06916	1.9	1.8	4E4	4.67	.13	6.40	15.19	118.99		.95		29	30						
21.0	22.5	06917	1.5	1.5	4E4	4.09	.02	5.79	13.00	109.00		.89	1	21	23						
22.5	23.3	06918	.8	.8	4E51	2.89	.02	3.70	8.40	63.99		1.10	1	20	21						







DDH: FAGU089

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAO %	HG %	MN %	AS %	BA %	S.G. W.R.
.0	1.1	07056	1.1	1.1	4L12	3.08	.07	.72	2.06	15.99		.47	1	6	7						
1.1	3.0	07057	1.9	1.5	4C0	3.04	.11	.62	1.28	13.99		.95	1	7	8						
3.0	4.8	07058	1.8	1.8	4L12	3.10	.02	2.08	4.20	38.00	30.99	.47	1	1	2						
4.8	6.7	07059	1.9	1.9	4L12	2.93	.02	1.63	3.70	31.99		.47	1	1	2						
6.7	9.1	07060	2.4	2.4	4L12	3.02	.05	.75	1.13	13.99		.55	1	4	5						
9.1	11.0	07061	1.9	1.9	4L12	4.01	.08	.99	1.10	20.00		.47	1	6	7						
11.0	12.2	07062	1.2	1.2	4A10	2.91	.05	1.57	2.29	30.99		.81	1	4	5						
12.2	14.8	07063	2.6	2.6	4L12	2.89	.02	.40	2.00	31.99		.55	1	2	3						
14.8	15.2	07064	.4	.4	4D0	2.91	.02	1.73	4.59	26.00		.47	1	1	2						
15.2	16.8	07065	1.6	1.5	4L12	2.87	.02	2.02	4.79	39.00		.40	1	1	2						
16.8	18.3	07066	1.5	1.5	4L12	2.87	.02	1.42	2.79	27.00		.40	1	2	3						
18.3	19.8	07067	1.5	1.2	4E4	4.45	.17	8.69	15.99	126.99		1.70		26	27						
19.8	21.8	07068	2.0	1.3	4E4	4.73	.13	7.70	15.40	158.00	150.00	1.16		27	28						
21.8	24.1	07069	2.3	1.8	4E41	3.89	.02	7.59	17.19	145.00		1.37	1	17	19						
24.1	26.4	07070	2.3	2.2	4E4	4.38	.07	10.00	22.00	165.00		1.23	1	21	22						
26.4	26.9	07071	.5	.5	4A14	3.33	.11	1.86	5.90	31.99		.47	5	15	20						
26.9	28.4	07072	1.5	1.5	4E41	4.38	.10	8.50	16.60	155.00		1.16	2	14	17						
28.4	30.5	07073	2.1	.7	5A61	2.99	.02	.53	1.12	13.99		.14	1	3	5						
30.5	31.7	07074	1.2	.6	4E41	4.09	.11	8.69	12.80	170.00		1.58	2	18	20						

DDH: FAGU090

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	---ASSAYS---							S.G. W.R.		
FROM	TO												PO %	PY %	TOT FE	BAC %	HG %	MN %	AS %		BA %	
.0	3.0	11008	3.0	.7	4E4	4.67	.17	8.50	10.10	119.00		1.92	1	27	28							
3.0	6.1	11009	3.1	1.1	4E4	4.70	.22	9.20	19.70	138.00		2.40	1	23	25							
6.1	9.2	11010	3.1	1.6	4E4	4.63	.11	7.20	13.20	121.00		1.71	1	26	27							
9.2	12.2	11011	3.0	1.7	4E4	4.64	.25	6.60	10.90	113.00		2.06	1	28	29							
12.2	13.7	11012	1.5	1.5	4A4	3.70	.16	2.90	4.00	62.00		.89	1	20	21							
13.7	15.2	11013	1.5	1.0	4A4	4.29	.13	3.30	5.40	61.00		.96	1	21	22							
15.2	17.0	11014	1.8	1.2	4E4	3.49	.12	2.50	4.10	52.00	53.00	1.03	1	15	16							
17.0	18.3	11015	1.3	1.3	4A0	3.07	.01	.06	.07	4.00		.14	3	1	4							

DDH: FAGU091

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														S.G. W.R.	
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PG %	PY %	TOT FE	BAC %	HG %	MN %	AS %	BA %		
.0	3.0	11970	3.0	1.5	4A30	3.62	.08	1.93	2.70	46.00			1.16		21	22						
3.0	5.5	11971	2.5	2.5	4A30	3.27	.04	1.12	2.60	27.99			.75		13	14						
5.5	8.0	11972	2.5	2.4	4A34	3.41	.02	1.99	3.70	45.00			.95	1	15	16						
8.0	10.0	11973	2.0	1.9	4A1	3.00	.02	1.67	3.10	33.00			.89	1	6	7						
10.0	12.0	11974	2.0	2.0	4A14	2.98	.04	2.10	3.29	39.00			1.23		5	6						
12.0	14.0	11975	2.0	1.9	4A14	2.97	.02	2.10	4.29	35.00			.68		3	4						
14.0	16.0	11976	2.0	2.0	4A1	2.89	.02	1.24	2.39	20.00			1.10			1						
16.0	17.4	11977	1.4	1.4	4A1	2.85	.02	.46	1.27	7.99			.34									
17.4	19.4	11978	2.0	2.0	4D5	3.06	.05	3.29	4.20	54.00			1.23	1	6	7						
19.4	21.4	11979	2.0	2.0	4D5	2.85	.02	1.60	3.39	26.00			.62			1						
21.4	23.3	11980	1.9	1.9	4C5	2.83	.02	1.57	3.39	24.00	21.00		.62		4	5						
23.3	26.0	11981	2.7	2.7	4C5	2.83	.02	.55	.62	10.00			.55			1						
26.0	29.0	11982	3.0	1.2	4L41	2.87	.02	1.08	2.29	18.00			.47		1	2						
29.0	32.0	11983	3.0	2.7	4L41	2.95	.07	1.83	1.76	31.99			1.30		5	6						
32.0	35.0	11984	3.0	2.9	4L41	2.95	.07	1.30	1.06	25.00			.95	1	5	6						
35.0	37.5	11985	2.5	2.5	4L41	2.83	.02	.57	1.71	10.00			.55									
37.5	41.5	11986	4.0	2.4	4C0	2.91	.02	1.31	1.70	23.00			.62		4	5						
41.5	42.7	11987	1.2	1.0	4L41	2.91	.07	1.34	2.70	29.99			.63	1	3	5						
62.6	65.1	11988	2.5	2.3	4AE4	3.62	.22	3.00	4.90	48.00			1.70	1	19	21						
65.1	67.6	11989	2.5	2.1	4AE4	3.49	.13	2.10	3.89	39.00			1.78	1	21	22						
67.6	70.0	11990	2.4	2.4	4A0	2.89	.04	.68	1.03	15.99	11.00		.47		1	2						
70.0	72.0	11991	2.0	1.9	4A0		.04	.64	.63	3.00												
72.0	75.0	11992	3.0	.7	4A0		.07	.64	1.19	15.99												
75.0	77.7	11993	2.7	2.7	4L42		.08	.66	.92	15.99												
79.1	81.4	11994	2.3	2.1	4C0		.07	.45	.84	12.00												
81.4	83.3	11995	1.9	1.7	4L42	2.93	.08	.69	1.84	9.00			.34		6	6						
83.3	86.9	11996	3.6	3.5	4L42	2.85	.02	3.10	1.42	35.00			.47	2		3						
86.9	91.4	11997	4.5	2.5	4L42		.04	.61	.88	11.00												
91.4	94.4	11998	3.0	2.8	4L42		.04	.46	.56	3.00												
94.4	97.5	11999	3.1	3.1	4A34	3.08	.10	2.10	3.00	29.99			.47	9		10						

DDH: FAGU092

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														S.G. W.R.	
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAC %	HG %	MN %	AS %	BA %		
1.0	2.0	11132	1.0	1.0	4D4	3.90	.02	8.00	16.20	128.00			1.17	2	15	17						
2.0	3.3	11133	1.3	1.3	4E4	4.69	.17	9.40	13.50	166.00			2.81	1	27	29						
3.3	4.6	11134	1.3	1.3	4E4	3.41	.05	8.40	12.70	123.00			1.92	2	26	28						
4.6	6.1	11135	1.5	1.5	4D4	3.79	.01	9.10	15.10	139.00			1.51	1	12	14						
6.1	7.6	11136	1.5	1.5	4D4	3.67	.02	8.00	14.60	113.00			1.37	2	11	13						
7.6	8.9	11137	1.3	1.3	4E4	4.64	.06	10.00	18.30	126.00			1.51	2	24	26						
8.9	10.7	11138	1.8	1.8	4E4	4.73	.07	1.53	7.60	35.00			1.44	4	36	40						
10.7	11.0	11139	.3	.3	4E4	4.40	.03	.46	10.90	15.00			.82	11	25	37						
11.0	12.3	11140	1.3	1.3	4E4	4.40	.12	1.58	10.60	38.00	40.00		1.51	5	30	35						
12.3	12.7	11141	.4	.4	4E4	3.21	.02	.80	6.10	22.00	26.00		.89	3	21	25						
12.7	14.6	11142	1.9	.9	4E4*	4.83	.03	1.56	6.30	31.00			1.17	2	39	41						
14.6	16.6	11143	2.0	1.9	4E4*	4.86	.15	7.70	16.00	109.00			2.40	1	29	31						
16.6	18.1	11144	1.5	1.5	4E41	4.30	.10	7.30	12.30	107.00			2.74	2	21	23						
18.1	19.7	11145	1.6	1.1	4E41	4.25	.22	2.20	6.60	39.00			2.40	2	28	31						
19.7	21.2	11146	1.5	1.1	4D4	3.87	.08	2.80	6.30	53.00			1.78	2	23	25						
21.2	22.8	11147	1.6	1.3	4C3	3.71	.11	1.01	4.40	24.00			2.19	2	22	24						
22.8	24.4	11148	1.6	1.6	4E4	3.61	.09	1.11	4.00	29.00			1.78	1	20	22						
24.4	26.4	11149	2.0	2.0	4A34	3.69	.09	3.00	5.30	49.00			1.78	1	18	20						
26.4	28.4	11150	2.0	1.9	4A34	4.03	.16	3.10	5.60	52.00	53.00		2.13	1	24	25						
28.4	29.9	11301	1.5	1.5	4E4	4.08	.24	2.50	3.00	52.00			3.29	1	28	30						
29.9	31.4	11302	1.5	1.5	4E4	3.89	.18	.93	2.90	32.00			2.67	1	26	28						
31.4	32.8	11303	1.4	1.4	4A3	3.59	.14	2.00	4.00	43.00			1.71	1	19	21						
32.8	34.3	11304	1.5	1.5	4A3	3.82	.13	.40	1.31	16.00			1.37	2	27	29						
34.3	35.9	11305	1.6	1.6	4AE4	3.94	.21	2.30	4.10	43.00			2.33	1	24	26						
35.9	37.5	11306	1.6	1.6	4AE4	3.82	.20	3.40	5.90	56.00			2.26	2	21	23						
37.5	39.6	11307	2.1	2.1	4E14	3.82	.20	2.30	3.30	50.00			2.61	1	23	25						
39.6	41.7	11308	2.1	2.1	4E14	3.68	.10	2.40	2.90	46.00			1.44	1	21	23						
41.7	42.7	11309	1.0	.9	4A34	3.65	.06	1.62	2.90	35.00			.96	1	21	22						
42.7	44.0	11310	1.3	1.2	4AC3	3.67	.08	.71	1.64	24.00			1.30	2	23	25						
44.0	45.4	11311	1.4	1.2	4AC3	3.82	.10	.86	3.50	32.00			1.30	2	26	29						
45.4	46.6	11312	1.2	1.0	4B4	2.95	.01	2.70	6.00	34.00			.41	1	2	4						
46.6	47.7	11313	1.1	1.0	4B4	2.99	.02	4.00	5.20	50.00			.55	1	2	3						

DDH: FAGU093

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PC %	PY %	TOT FE	BAO %	HG %	MN %	AS %	BA %	S.G. W.R.
.0	3.0	12035	3.0	1.6	4A3	3.62	.11	1.53	2.89	37.00		1.10	1	22	23						
3.0	5.0	12036	2.0	1.7	4A14	3.33	.05	2.79	5.00	55.00		.95	1	24	26						
5.0	7.1	12037	2.1	1.2	4A14	3.54	.11	2.10	4.09	47.00		1.03	1	8	9						
7.1	9.6	12038	2.5	2.3	4D5	3.41	.05	2.79	4.20	49.00		.89	1	20	21						
9.6	12.2	12039	2.6	2.6	4D5	3.37	.05	2.70	3.89	46.00		1.10	1	15	16						
12.2	14.2	12040	2.0	2.0	4C5	3.43	.07	1.73	3.00	27.99		.81	1	16	17						
14.2	15.9	12041	1.7	1.7	4C5	2.95	.02	1.25	3.10	15.99		.34		18	19						
15.9	18.0	12042	2.1	1.8	4C0	3.00	.04	1.27	3.49	26.00		.55		4	5						
18.0	19.8	12043	1.8	1.8	4A0	2.85	.02	1.57	3.29	26.00		.40		5	6						
19.8	22.8	12044	3.0	2.8	4C5	2.87	.05	1.69	3.29	27.00		.81		1	2						
22.8	24.8	12045	2.0	2.0	4C0	3.04	.08	1.12	1.14	24.00		1.23		2	3						
24.8	26.3	12046	1.5	1.5	4C0	2.91	.05	1.54	2.50	27.00		.62		8	9						
26.3	27.4	12047	1.1	1.0	4L12	2.95	.05	1.57	1.87	26.00		1.16		3	4						
43.9	46.7	12048	2.8	2.5	4A4	3.27	.07	3.20	5.70	48.00		1.03	2	4	6						
46.7	48.8	12049	2.1	2.0	4L4	2.95	.05	2.02	3.89	35.00		.47	3	8	11						
48.8	49.6	12050	.8	.8	4D0	2.87	.02	2.14	5.40	34.00	34.00	.40	1	12	14						
49.6	52.3	12051	2.7	1.3	4L14	2.85	.02	.99	2.60	23.00		.55		5	6						
52.3	54.3	12052	2.0	2.0	4L14	3.02	.08	.69	1.55	10.00		1.10	1	2	3						
54.3	57.0	12053	2.7	2.6	4L21	2.95	.07	.53	.99	12.00		.47	2	6	8						
57.0	59.5	12054	2.5	1.9	4B0	2.89	.05	1.66	1.20	21.00		.34	2	4	6						
59.5	61.5	12055	2.0	1.6	4A0	3.12	.02	1.10	2.79	27.99		.81	1	2	3						
61.5	63.1	12056	1.6	1.4	4A0	3.27	.05	1.44	2.60	29.99		.95	1	10	11						
63.1	64.8	12057	1.7	1.6	4A4	3.35	.08	2.04	4.70	37.00		1.30	1	15	16						
64.8	65.7	12058	.9	.9	4A4	3.43	.10	3.70	6.59	67.00		1.78	1	14	16						
65.7	67.1	12059	1.4	1.1	4E41	3.12	.14	7.09	13.50	108.00		1.85	2	10	12						

DDH: FAGU095

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														S.G. W.R.
FROM	TO						CU. %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAC %	HG %	MN %	AS %	BA %	
.0	3.8	12168	3.8	1.6	4A4	3.10	.05	3.20	4.29	55.00		.62	1	6	8						
3.8	6.7	12169	2.9	.0	4A43	3.35	.05	3.79	4.90	72.00		1.03	1	13	15						
6.7	9.1	12170	2.4	.0	4A43	3.24	.04	2.39	5.20	48.00		.75	1	12	14						
9.1	12.0	12171	2.9	.0	4A43	3.14	.04	1.60	3.99	34.00		.68	1	12	13						
12.0	14.6	12172	2.6	.0	4A43	3.24	.04	3.89	7.29	72.00		.75	1	10	12						
14.6	15.4	12173	.8	.0	4D45	3.31	.02	6.90	11.50	138.00		.95	2	9	11						
15.4	17.2	12174	1.8	.0	4A3	3.29	.04	1.46	3.20	33.00		.75	1	11	13						
17.2	19.6	12175	2.4	.0	4A43	3.33	.05	1.73	3.60	38.00		1.23	1	15	16						
19.6	20.5	12176	.9	.0	4L3	2.81	.02	.35	.62	10.00		.27	1	3	5						
20.5	22.3	12177	1.8	.0	4E4	3.83	.02	6.29	10.00	115.99	110.00	1.91	1	14	16						
22.3	24.0	12178	1.7	.0	4E41	3.74	.02	6.50	9.09	105.00		1.10	2	18	20						
24.0	25.5	12179	1.5	.0	4A0	2.93	.01	.27	.28	7.99		.34		5	6						
25.5	27.7	12180	2.2	.0	4G4	3.60	.05	2.79	8.59	57.99		.40	1	17	18						
27.7	28.6	12181	.9	.0	4L3	3.43	.01	.33	.99	12.00		.55	1	14	16						
28.6	30.7	12182	2.1	.0	4G0	3.62	.01	1.84	6.29	40.00		.47	2	19	21						
30.7	32.0	12183	1.3	.0	4A0	2.87	.01	.82	1.85	18.00		.47	1	4	5						
38.3	41.1	12184	2.8	.0	4EK4	3.81	.04	5.40	13.90	94.00		1.10	2	17	19						
41.1	42.9	12185	1.8	.0	4AD4	3.39	.08	5.40	12.80	94.00		1.58	3	11	14						
42.9	45.2	12186	2.3	.0	4A34	3.31	.08	4.79	7.20	78.00		1.98	2	11	14						
45.2	47.2	12187	2.0	.0	4AD	3.52	.14	3.00	3.99	50.00	50.00	3.49	2	15	17						
50.3	52.6	12188	2.3	.0	4A43	3.39	.10	2.79	4.20	50.00		1.43	2	18	20						
52.6	54.9	12189	2.3	.0	4A43	2.97	.05	2.70	3.20	43.00		.89	2	7	9						
110.5	113.0	12190	2.5	.0	4A0	3.12	.08	.16	.40	10.00		.68	1	12	14						
113.0	115.2	12191	2.2	.0	4A0	2.91	.05	1.57	2.29	35.00		.81	2	7	9						
115.2	117.2	12192	2.0	.0	4E46	4.38	.20	5.90	8.30	103.00		1.64	1	28	29						
117.2	119.3	12193	2.1	.0	4E46	4.45	.17	4.40	5.09	95.00		1.43	1	34	35						

DDH: FAGU096

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														S.G. W.R.	
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAC %	HG %	MN %	AS %	BA %		
1.0	3.0	11401	2.0	1.0	4E4*	5.36	.21	5.30	12.20	105.00			2.26	2	31	33						
3.0	4.6	11402	1.6	.3	4E4*	5.03	.06	4.10	12.90	52.00			.96	1	34	35						
4.6	6.0	11403	1.4	1.2	4E4*	4.91	.11	4.50	15.10	64.00			1.51	2	29	31						
6.0	7.4	11404	1.4	.8	4E4*	5.03	.12	3.90	12.10	73.00			1.51	2	33	35						
7.4	9.3	11405	1.9	1.9	4D4	4.25	.07	8.50	16.20	126.00			1.65	2	16	18						
9.3	10.4	11406	1.1	1.1	4E4*	5.01	.26	6.20	13.70	105.00			2.47	1	28	29						
10.4	11.2	11407	.8	.8	4D4*	4.01	.02	7.50	15.80	117.00			1.37	1	15	16						
11.2	13.0	11408	1.8	1.8	4A34	4.42	.06	7.10	12.90	108.00			2.26	1	19	21						
13.0	14.8	11409	1.8	1.8	4A34	3.73	.03	4.30	11.10	70.00			1.44	2	9	12						
14.8	16.7	11410	1.9	1.9	4A34	3.66	.05	5.50	11.20	90.00	86.00		2.06	2	14	16						
16.7	18.6	11411	1.9	1.9	4K0	5.03	.09	.61	4.30	22.00			2.26	4	36	40						
18.6	19.3	11412	.7	.7	4A14	3.89	.14	1.82	5.10	48.00			2.13	1	19	21						
19.3	20.0	11413	.7	.7	4E0	4.99	.11	.95	2.80	23.00			2.13	1	31	32						
20.0	20.3	11414	.3	.3	4E0	3.84	.08	1.72	2.70	32.00			1.51	1	26	27						
20.3	21.5	11415	1.2	1.2	4A3	3.85	.09	.85	2.50	24.00			1.71	1	26	27						
21.5	22.7	11416	1.2	1.1	4A3	3.77	.04	.97	3.30	25.00			.89	1	15	17						
22.7	24.4	11417	1.7	1.7	4A1	3.02	.02	.42	.88	13.00			.48	1	6	7						
24.4	26.1	11418	1.7	1.7	4A1	3.12	.03	1.18	3.20	23.00			.69	1	7	9						
26.1	28.1	11419	2.0	2.0	4E4	3.96	.11	2.90	5.50	48.00			1.92	1	24	25						
28.1	30.4	11420	2.3	2.2	4A14	3.61	.10	3.30	3.90	48.00	48.00		1.65		18	19						
30.4	31.5	11421	1.1	1.1	4A3	3.99	.12	1.01	.95	25.00			1.78	1	25	26						
31.5	32.2	11422	.7	.6	4E1	3.85	.10	2.40	3.00	39.00			1.44	1	23	25						
32.2	33.7	11423	1.5	1.5	4A14	2.93	.02	1.26	3.30	19.00			.34	1	1	3						
33.7	35.3	11424	1.6	1.5	4A14	2.90	.01	1.89	3.70	29.00			.41			1						
35.3	36.2	11425	.9	.8	5C46	3.01		.49	.93	11.00			.14	3	3	6						
36.2	37.7	11426	1.5	1.5	4L14	3.02		1.93	3.90	34.00			.48	1	2	3						
39.2	40.4	11427	1.2	.9	4L3	2.99		1.72	3.30	36.00			.48	2	5	7						
40.4	41.7	11428	1.3	.6	4L3	2.92		.56	.47	12.00			.34	2	4	6						
41.7	43.5	11429	1.8	.7	4L14	3.00		1.01	1.86	22.00	25.00		.41	1	4	6						
43.5	45.4	11430	1.9	.8	4L14	2.92		1.31	2.30	35.00			.48	1	4	6						
45.4	47.3	11431	1.9	1.2	4L14	2.90		.66	1.09	17.00			.14	2	2	5						
47.3	48.8	11432	1.5	.8	4A31	3.28		1.42	3.20	34.00			.69	2	13	15						
48.8	50.3	11433	1.5	.8	4A31	3.02		.60	1.62	16.00			.27	3	6	10						
50.3	51.8	11434	1.5	.6	4A31	2.85		1.38	1.65	19.00			.27	1	1	3						
53.2	56.4	11435	3.2	.6	4A1	2.88		1.29	1.86	22.00			.21	2	1	3						
56.4	57.9	11436	1.5	1.2	5B9	2.85		.50	1.52	11.00			.21	1		2						
57.9	59.5	11437	1.6	1.6	5B9	2.91		.55	1.13	12.00			.34	1	1	2						
59.5	61.2	11438	1.7	1.0	5B9	2.93		.21	.36	10.00			.14	5	1	6						
97.9	99.0	11439	1.1	.7	4A14	3.42		3.30	2.40	48.00			.69	1	15	16						
99.0	99.8	11440	.8	.7	4A4	3.47		3.70	7.87	51.00			1.10	2	9	11						
99.8	101.7	11441	1.9	1.0	4E4	4.45		8.30	16.00	139.00	131.00		1.10		25	26						
101.7	103.7	11442	2.0	2.0	4E4	4.42		8.10	17.70	122.00			.89	1	22	23						
103.7	104.0	11443	.3	.3	4E4	3.78		7.70	16.70	130.00			1.20	2	12	15						
37.7	39.2	11444	1.5	1.5	4L14	3.03		2.90	6.30	47.00			.48	2	3	5						

DDH: FAGU097

						-----ASSAYS-----															
DEPTHS	SAMPLE	INT.	REC.	ROCK	S.G.	CU	PB	ZN	AG(AA)	AG(FA)	AU(FA)	PO	PY	TOT	BAC	HG	MN	AS	BA	S.G.	
FROM	TO	NO.		UNIT	PULP	%	%	%	G/MT	G/MT	G/MT	%	%	FE	%	%	%	%	%	W.R.	
.0	3.0	12060	3.0	1.4	4A34	3.45	.04	3.20	6.00	68.00				.89	1	19	20				
3.0	4.6	12061	1.6	1.0	4A34	3.62	.07	3.29	4.79	59.99				1.30	1	14	16				
4.6	6.6	12062	2.0	2.0	4A43	3.35	.04	2.89	3.60	50.00				1.03	1	19	20				
6.6	8.6	12063	2.0	1.8	4A43	3.24	.02	1.89	4.29	44.00				.40	1	15	16				
8.6	10.6	12064	2.0	1.9	4A3	3.39	.02	1.10	2.79	29.99				.89	1	11	12				
10.6	12.6	12065	2.0	1.4	4A3	3.14	.02	1.29	2.89	27.99				.55	1	17	18				
12.6	14.6	12066	2.0	1.6	4A43	3.16	.02	1.18	4.59	28.99				.55	1	9	11				
14.6	16.6	12067	2.0	1.9	4A3	3.50	.02	.84	3.99	26.00				.62	1	16	18				
16.6	18.6	12068	2.0	1.6	4A43	3.24	.02	2.29	5.00	35.00				.75	1	10	12				
18.6	21.3	12069	2.7	.8	4A34	3.47	.02	1.87	6.09	40.00				.75	1	14	15				
21.3	23.3	12070	2.0	1.5	4A4	3.24	.02	1.10	4.40	29.99	23.00			.55	1	24	25				
23.3	25.3	12071	2.0	1.7	4A4	3.25	.02	1.13	3.89	31.99				.81	1	12	13				
25.3	27.3	12072	2.0	1.9	4A4	3.22	.02	2.10	5.79	55.00				.81	1	10	12				
27.3	29.3	12073	2.0	1.4	4A0	3.04	.02	1.51	3.20	40.00				.62	1	7	8				
29.3	31.3	12074	2.0	1.1	4A4	3.22	.02	2.60	5.40	67.00				.81	1	10	11				
31.3	33.3	12075	2.0	2.0	4A4	2.95	.02	1.80	4.20	44.00				.62	1	4	5				
33.3	35.3	12076	2.0	1.6	4A4	2.95	.01	3.00	5.79	61.99				.75	1	2	3				
35.3	37.0	12077	1.7	1.4	4A4	2.95	.02	2.02	3.89	47.00				.68	1	3	4				
37.0	39.6	12078	2.6	2.6	4D5	3.04	.02	2.39	6.09	55.00				.62	1	5	6				
39.6	42.3	12079	2.7	2.1	4D5	3.14	.02	3.29	6.50	71.00				.68	1	6	7				
42.3	44.7	12080	2.4	1.1	4E4	4.17	.05	4.09	12.90	74.00	70.00			1.30	4	19	24				
44.7	46.7	12081	2.0	1.4	4A30	3.37	.11	1.11	2.89	29.99				1.58	2	15	17				
46.7	48.4	12082	1.7	1.5	4A34	3.47	.11	1.93	3.99	35.00				1.58	2	14	17				







DDH: FAGU101

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAO %	HG %	MN %	AS %	BA %
.0	2.7	12116	2.7	.5	4D4	3.64	.04	5.59	7.90	94.00		.81	4	12	16					
2.7	4.2	12117	1.5	1.5	4D0	3.43	.02	2.29	5.50	52.00		.55	2	8	10					
54.9	55.8	12118	.9	.8	4GE4	3.83	.08	9.50	17.60	166.00		1.03	2	6	9					
55.8	58.0	12119	2.2	2.0	4A43	3.22	.07	2.79	3.60	56.99		1.03	3	6	9					
58.0	60.5	12120	2.5	2.5	5D4@	3.45	.05	3.79	3.29	56.99		1.10	2	11	14					
60.5	63.1	12121	2.6	2.6	5D4@	3.33	.05	3.29	3.70	55.99		.75	3	7	11					
63.1	65.6	12122	2.5	2.5	4A4	3.49	.04	4.40	5.29	73.00		1.10	1	12	14					
67.7	69.2	12123	1.5	1.3	4AD	3.14	.02	2.29	3.60	38.00		.62	2	6	8					
69.2	70.6	12124	1.4	1.4	4A0	2.95	.02	.96	2.50	25.00		.40	1	2	4					
70.6	72.3	12125	1.7	1.7	4A41	3.41	.04	3.10	3.60	53.00		.89	2	11	14					
72.3	74.0	12126	1.7	1.3	4A1	3.35	.02	1.57	2.29	30.99		.75	3	9	13					
74.0	76.8	12127	2.8	2.0	4A0	2.99	.01	.55	1.88	10.00		.20	2	2	4					
76.8	79.3	12128	2.5	2.3	4A0	2.95	.01	.83	2.29	20.00		.27	2	2	4					
79.3	80.8	12129	1.5	1.3	5A94	2.93	.01	1.65	3.70	36.00		.62	2	1	3					
80.8	82.1	12130	1.3	1.3	4A0	2.93	.01	.86	1.97	19.00		.62	2	4	6					
82.1	84.5	12131	2.4	2.4	5B6	2.93	.01	.55	.64	11.00		.55	2	4	6					
84.5	86.8	12132	2.3	2.3	4A31	3.02	.02	1.59	2.79	31.99		.95	1	5	6					
86.8	88.9	12133	2.1	2.1	5B62		.01	.04	.07	.99										
88.9	90.6	12134	1.7	1.7	5A6	2.93	.01	.77	1.26	19.00		.14	2	2	4					
90.6	93.6	12135	3.0	2.9	4A03	3.14	.04	1.38	2.60	29.99		.81	1	10	11					
93.6	95.2	12136	1.6	1.6	5B6		.01	.08	.11	3.00										
95.2	98.1	12137	2.9	2.4	5B6		.01	.61	.90	11.00										
98.1	99.1	12138	1.0	.7	4E4*	4.28	.14	6.79	12.40	130.00	117.99	1.64	1	23	24					
131.1	133.9	12139	2.8	2.7	4A0		.07	.10	.17	3.99										
133.9	134.8	12140	.9	.8	4AC	3.00	.10	.02	.05	5.00	.99	.27	4	6	11					
134.8	137.3	12141	2.5	2.4	4A0		.07	.04	.11	1.99										
137.3	138.7	12142	1.4	1.4	4A0		.05	.72	1.52	13.99										
138.7	140.0	12143	1.3	1.2	4A0		.11	.05	.10	5.00										
140.0	142.0	12144	2.0	2.0	4AC0		.11	.07	.22	5.00										
142.0	143.4	12145	1.4	1.2	5D\$		.01	.02	.07	3.00										
143.4	145.7	12146	2.3	1.7	4A4	3.24	.05	1.94	3.20	36.00		1.03	1	11	13					
145.7	147.8	12147	2.1	1.9	4G45	3.64	.05	3.39	7.49	62.99		1.10	1	17	18					
147.8	149.0	12148	1.2	1.2	4A0	3.10	.02	1.26	3.00	26.00		.47	2	6	9					



DDH: FAGU103

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAC %	HG %	MN %	AS %	BA %
.0	2.4	12149	2.4	1.2	4A4	3.72	.02	5.20	9.40	97.00		2.06	2	14	17					
2.4	4.6	12150	2.2	1.2	504B	3.04	.02	1.95	3.89	34.00		.27	4	3	8					



DDH: FAGU105

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														S.G. W.R.	
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAG %	HG %	MN %	AS %	BA %		
.0	3.8	12194	3.8	3.0	4K0	3.10	.02	.52	1.25	13.99		.07	7	5	13							
3.8	5.8	12195	2.0	1.6	5D4@	3.45	.01	.67	1.36	21.00		.20	5	14	20							





DDH: FAGU108

						-----ASSAYS-----															
DEPTHS	SAMPLE	INT.	REC.	ROCK	S.G.	CU	PB	ZN	AG(AA)	AG(FA)	AL(FA)	PO	PY	TOT	BAC	HG	MN	AS	BA	S.G.	
FROM	TO	NO.		UNIT	PULP	%	%	%	G/MT	G/MT	G/MT	%	%	FE	%	%	%	%	%	W.R.	
10.9	12.8	11255	1.9	1.9	4A0	3.10	.12	.63	1.37	21.00					.69	1	11	12			
54.5	55.9	11256	1.4	1.4	4G4*	4.66	.03	7.10	9.50	113.00					.48	1	17	18			
55.9	57.9	11257	2.0	1.8	4E4*	4.29	.09	6.50	8.30	103.00					.55	1	16	18			
57.9	59.5	11258	1.6	.5	4E4*	4.43	.10	5.40	8.30	94.00					.55	1	16	17			
59.5	60.6	11259	1.1	.7	4E4*	4.40	.09	5.70	8.30	95.00					.75	3	27	30			
60.6	61.6	11260	1.0	.9	4D4	3.86	.12	6.20	7.00	88.00					.82	5	17	23			
61.6	64.0	11261	2.4	2.2	4C3	3.72	.16	.89	1.27	24.00					1.45	3	22	26			
64.0	64.5	11262	.5	.5	4D4	3.67	.10	4.30	5.80	58.00					1.44	3	16	19			
64.5	65.0	11263	.5	.5	4A14	3.77	.10	3.40	3.60	37.00					1.78	2	18	20			
65.0	66.5	11264	1.5	1.5	4A13	3.74	.24	1.35	1.35	27.00					2.54	1	24	26			
66.5	68.9	11265	2.4	1.4	4C3	3.79	.30	.99	1.40	26.00	26.00				1.17	1	24	25			
68.9	70.5	11266	1.6	1.1	4E1		.30	.17	.60	13.00											
70.5	72.1	11267	1.6	1.4	4E1		.38	.43	.77	18.00											
.0	3.0	11445	3.0	1.1	4D4	3.74		9.00	20.20	136.00					.69	1	8	10			
3.0	4.6	11446	1.6	.7	4E4*	4.86	.05	2.90	6.50	50.00					1.03		37	38			
4.6	6.1	11447	1.5	.8	4E4*	4.82	.20	3.90	6.60	110.00					2.06		34	35			
6.1	8.7	11448	2.6	1.1	4E4*	4.80	.10	7.60	14.20	127.00					1.78	1	27	28			
8.7	9.0	11449	.3	.2	4A0	3.68	.09	1.19	1.59	32.00					1.03	1	22	24			
9.0	10.9	11450	1.9	1.9	4A0	3.33	.10	.91	1.71	24.00					.69	1	13	14			

DDH: FAGU109

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													S.G. W.R.		
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAC %	HG %	MN %	AS %		BA %	
.0	3.0	12196	3.0	1.5	4A4	3.22	.02	1.65	4.59	44.00		.34	2	10	13							
3.0	4.6	12197	1.6	1.2	4A4	3.47	.02	4.79	12.19	127.99		.95	3	10	13							
50.9	53.3	12198	2.4	2.4	4A43	3.58	.05	4.79	8.80	89.00		.95	1	15	17							
67.3	69.2	12199	1.9	1.7	4D0	3.31	.10	2.39	4.09	50.00		1.51	2	12	14							
69.2	71.2	12200	2.0	1.8	4ECA	3.41	.10	2.70	3.49	52.00		1.30	4	16	20							
71.2	73.2	12201	2.0	1.9	4D0	2.93	.02	1.77	4.20	34.00		.68	2	3	6							
73.2	74.8	12202	1.6	1.5	5D*	2.93	.01	.26	.38	11.00		.20	4	1	6							
74.8	76.7	12203	1.9	1.7	4A43	3.45	.11	2.79	4.79	53.00		1.66	1	17	18							
76.7	78.3	12204	1.6	1.6	4E4	4.17	.16	5.50	11.00	112.99		2.39	2	24	27							
78.3	79.7	12205	1.4	1.1	4L25	3.20	.05	1.22	2.50	36.00		.34	5	6	11							
90.8	91.7	12206	.9	.8	4D0	2.91	.02	2.79	2.39	47.00		.27	3	2	6							
91.7	92.6	12207	.9	.8	5D\$	2.87	.01	.02	.28	7.99		.47	5		6							
92.6	95.5	12208	2.9	2.5	4D0	2.89	.02	1.70	3.79	37.00		.68	3	2	6							
95.5	97.3	12209	1.8	1.8	4D0	2.93	.05	2.20	4.20	49.00		.81	2	3	5							
97.3	98.7	12210	1.4	1.1	5D4B	2.87	.01	.05	.38	7.99		.14	6		7							
98.7	100.5	12229	1.8	1.8	4A0	3.04	.05	1.13	2.70	21.00		.14	6	5	11							

DDH: FAGU110

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														S.G. W.R.	
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAO %	HG %	MN %	AS %	BA %		
55.1	57.9	07291	2.8	.6	4A4	2.99	.01	1.95	3.49	38.00		.40	1	4	6							
57.9	61.4	07292	3.5	3.3	4AC	3.33	.05	3.60	4.59	65.00		1.16	2	10	12							
61.4	64.6	07293	3.2	2.7	4A0	3.22	.08	1.82	2.70	37.00		.62	5	8	13							
64.6	66.7	07294	2.1	1.4	5A19	2.98	.02	1.06	2.02	12.00	12.00	.62	3	4	7							







DDH: FAGU115

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													S.G. W.R.	
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAO %	HG %	MN %	AS %		BA %
8.5	10.7	11124	2.2	1.5	4E4	4.94	.14	6.00	9.60	156.00		1.92		30	31						
10.7	13.7	11125	3.0	1.2	4E4	5.26	.10	4.40	9.10	93.00		1.58	1	34	35						
13.7	15.5	11126	1.8	.7	4D4	3.84	.07	5.00	12.50	99.00		1.23	1	13	14						
15.5	17.6	11127	2.1	2.0	4E4	5.01	.15	2.90	4.60	51.00		1.17	1	39	40						
17.6	19.1	11128	1.5	1.4	4E4	4.83	.11	5.40	9.70	105.00		1.30	1	31	32						
19.1	22.2	11129	3.1	1.3	4A0	3.46	.09	2.60	4.20	45.00	49.00	.96	1	12	13						
24.6	27.0	11130	2.4	2.4	4A0	3.49	.09	.93	.93	25.00		.55		13	14						
27.0	30.2	11131	3.2	2.0	4A4	3.66	.08	2.60	4.90	42.00	40.00	.55	1	13	14						
2.0	3.8	11227	1.8	1.7	4D4	3.81	.05	4.90	11.30	83.00		1.37	1	20	21						
3.8	5.5	11249	1.7	1.1	4D4	3.77	.03	5.80	12.00	117.00		.55	1	12	13						
5.5	8.5	11250	3.0	.6	4E4	4.70	.05	3.00	7.30	60.00		.69	1	31	32						



DDH: FAGU117

-----DEPTHS-----			-----ASSAYS-----																			
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAG %	HG %	MN %	AS %	BA %	S.G. W.R.	
.0	2.4	08750	2.4	.9	4A14	3.38	.03	1.91	4.10	47.00		.75	1	16	17							
2.4	4.8	08751	2.4	2.0	4A14	3.66	.02	1.24	3.90	35.00		.89	1	24	25							
4.8	7.2	08752	2.4	2.4	4A14	3.25	.03	1.30	3.70	33.00		.82		14	15							
7.2	9.6	08753	2.4	2.3	4A14	3.33	.04	2.40	6.20	46.00		.89	1	14	15							
15.7	17.4	08754	1.7	1.3	4ECO	3.52	.06	1.36	3.00	35.00		1.58	2	17	19							
17.4	18.1	08755	.7	.7	4A4	3.08	.01	4.40	7.30	75.00		.89	1	6	7							
18.1	18.6	08756	.5	.5	4D4	3.15	.01	4.30	7.20	71.00		.75	1	7	8							
18.6	19.2	08757	.6	.6	5D4	2.95	.07	.52	1.20	10.00		.27	3	2	6							
19.2	19.8	08758	.6	.6	4A4	4.12	.01	6.80	6.90	101.00	105.00	1.58	1	13	15							
19.8	20.4	08759	.6	.6	5D4	2.87	.04	.13	.13	5.00		.21	4	1	5							
20.4	21.8	08760	1.4	1.3	4D45	3.37	.02	6.00	11.10	100.00		.75	2	8	11							
21.8	22.9	08761	1.1	1.1	5D4	2.88	.02	.18	.21	8.00		.27	5	1	6							
22.9	23.4	08762	.5	.5	4DE	3.49	.06	3.70	9.70	66.00		.89	1	13	15							

DDH: FAGU118

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														S.G. W.R.	
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAC %	HG %	MN %	AS %	BA %		
.0	1.5	07598	1.5	.5	4H0		.05	.42	1.04	17.00												
1.5	2.9	07599	1.4	1.2	4AD4	3.43	.02	5.59	10.69	93.00		1.03	3	8	11							
2.9	4.1	07600	1.2	1.2	4E4#	4.04	.02	2.29	6.79	51.00		1.85	3	27	30							
4.1	6.1	07601	2.0	1.8	4KDL	3.49	.01	2.39	6.09	42.00		1.03	3	12	15							
6.1	8.7	07602	2.6	2.6	4KD	3.56	.05	5.50	12.40	127.99		1.51	3	11	14							
8.7	10.6	07603	1.9	1.1	4K4	4.30	.11	10.09	19.60	249.99		2.25	1	17	18							
13.7	14.3	07604	.6	.6	4L04	3.12	.02	3.49	4.59	59.99		.81	4	4	8							
14.3	16.6	07605	2.3	2.1	4K4	3.79	.01	4.40	9.69	90.00		1.30	3	17	20							
21.3	23.3	07606	2.0	1.5	4A0	3.41	.05	1.20	3.29	29.99		1.37	1	17	18							
23.3	25.1	07607	1.8	1.5	4A4	3.37	.05	2.39	5.50	44.00		1.23	1	15	16							
25.1	25.5	07608	.4	.4	4D4	3.83	.17	6.20	7.99	117.99	113.99	1.37	1	20	21							
25.5	28.0	07609	2.5	2.0	4A4	3.49	.08	6.59	13.59	117.99		1.78	2	9	12							
28.0	30.0	07610	2.0	1.5	4L14	3.14	.05	1.99	2.50	36.00		.95	2	10	12							
30.0	31.5	07611	1.5	1.3	4L1		.17	.14	.54	7.99												
39.6	41.1	07612	1.5	1.3	4L4	3.18	.08	4.29	7.90	66.00		1.37	1	8	9							
41.1	42.6	07613	1.5	1.0	4L4	2.48	.08	3.79	8.50	57.99		1.10	1	2	4							
42.6	44.1	07614	1.5	1.3	4A0	3.35	.19	.94	1.87	23.00		1.23	1	19	20							
44.1	46.1	07615	2.0	1.5	4L4	3.02	.08	1.70	3.89	38.00		.95	1	5	7							
46.1	48.1	07616	2.0	1.6	4L4	3.04	.07	1.05	2.89	23.00		1.16	1	7	9							
48.1	50.1	07617	2.0	2.0	4L4	3.02	.04	3.39	3.49	45.00		1.43	1	5	6							
50.1	52.0	07618	1.9	1.6	4L4	2.91	.08	1.56	2.79	26.00		.95		4	5							
52.0	53.9	07619	1.9	1.9	4L4	2.89	.04	1.65	1.64	26.00	24.00	.81	1	3	4							
53.9	55.4	07620	1.5	1.5	4A0	3.29	.14	1.28	2.70	30.99		1.51	1	14	16							
55.4	56.5	07621	1.1	.8	4D46	3.02	.19	6.79	14.30	116.99		1.78	2	14	17							







DDH: FAGU124

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														S.G. W.R.
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAG %	HG %	MN %	AS %	BA %	
.0	1.5	07656	1.5	.5	4A1	2.99	.49	1.55	1.79	25.00		1.03	1	5	7						
1.5	4.6	07657	3.1	2.6	4A14	3.20	.05	2.08	4.50	38.00		.89	1	8	9						
4.6	6.6	07658	2.0	1.9	4A1	2.89	.02	1.08	3.60	19.00		.55	1	1	3						
6.6	8.6	07659	2.0	1.4	4A14	3.02	.02	1.62	3.60	25.00		.55		1	2						
8.6	10.6	07660	2.0	1.6	4A14	3.10	.02	1.83	3.89	26.00		.47		1	1						
10.6	12.2	07661	1.6	1.5	4A14	3.33	.05	2.60	5.09	40.00		.68	1	3	4						
12.2	14.2	07662	2.0	2.0	4D0	3.29	.01	3.00	6.50	51.00		.81	1	7	9						
14.2	16.2	07663	2.0	2.0	4D4	3.49	.05	5.20	7.90	74.00		1.37	13	1	15						
16.2	18.2	07664	2.0	2.0	4D4	3.49	.05	5.29	9.09	86.00		1.30	1	8	9						
18.2	19.7	07665	1.5	1.3	4D4	3.41	.04	5.40	7.79	82.00		1.10	1	11	12						
19.7	20.8	07666	1.1	1.1	4A3	3.41	.08	.96	2.60	21.00		1.03	1	14	16						
25.9	27.9	07667	2.0	1.8	4C@	3.58	.17	1.64	3.20	43.00		1.98	1	18	19						
27.9	29.5	07668	1.6	1.5	4D@	3.56	.16	2.70	4.29	62.99		1.91	1	17	18						
29.5	30.4	07669	.9	.9	4L0	2.93	.02	.08	.20	5.00		.47	1	3	5						
30.4	32.7	07670	2.3	2.3	4A3	3.39	.08	1.45	1.69	40.00		1.64	1	15	16						
32.7	34.1	07671	1.4	1.4	4A34	3.52	.11	2.60	3.60	51.00		2.66	2	13	16						
34.1	34.8	07672	.7	.7	4D0	3.00	.08	3.20	5.90	58.99		2.33	1	20	22						
34.8	37.5	07673	2.7	2.7	4A14	3.54	.13	3.29	4.29	58.99	58.99	2.60	1	17	19						
38.7	39.6	07674	.9	.9	4D@4	3.31	.20	2.70	7.99	36.00		1.23	4	6	10						
39.6	42.3	07675	2.7	2.7	4D4	4.40	.10	15.49	27.00	253.99		1.78	1	10	11						
42.3	43.0	07676	.7	.7	4A0	3.02	.02	1.16	.27	22.00		.47		3	4						
44.9	46.5	07677	1.6	1.6	4K14	3.95	.10	5.59	17.69	108.00		.81	5	11	16						
46.5	47.5	07678	1.0	1.0	4AL4	3.24	.08	2.60	3.70	41.00		1.10	2	8	11						
47.5	49.2	07679	1.7	1.7	4AE4	4.05	.08	8.40	6.20	114.99		2.54	1	21	22						
49.2	51.9	07680	2.7	2.7	4AD4	3.64	.08	4.29	5.59	56.99		1.78	2	17	19						
51.9	54.5	07681	2.6	2.5	4LA	2.95	.05	1.03	2.39	15.99		.47	1	3	5						

DDH: FAGU125

-----DEPTHS-----			-----ASSAYS-----																			
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAC %	HG %	MN %	AS %	BA %	S.G. W.R.	
.0	1.5	11314	1.5	.5	4E4	4.49	.23	13.20	26.80	141.00		2.06	1	15	17							
1.5	3.9	11315	2.4	1.8	4E4	4.70	.18	6.50	11.40	113.00		1.58	2	30	32							
3.9	7.0	11316	3.1	1.6	4E4	4.69	.14	4.70	8.30	95.00		1.37	3	32	35							
7.0	10.0	11317	3.0	2.1	4E4	4.94	.16	5.00	8.60	110.00		1.51	2	22	25							
10.0	12.5	11318	2.5	1.3	4E4	4.93	.06	5.50	12.20	92.00		1.17	2	30	33							
12.5	14.6	11319	2.1	1.0	4D4	3.92	.05	4.60	11.50	83.00		.69	2	19	21							
14.6	16.2	11320	1.6	1.5	4D4	3.74	.03	7.60	17.70	133.00		.89	2	8	10							
16.2	18.2	11321	2.0	2.0	4D4	3.69	.18	8.80	16.40	160.00		1.58	2	9	12							
18.2	20.4	11322	2.2	2.2	4D4	3.90	.04	8.60	23.00	153.00	151.00	1.51	2	9	11							
20.4	22.1	11323	1.7	1.5	4D4	4.07	.03	10.00	25.40	166.00		1.03	3	8	11							
22.1	23.3	11324	1.2	.6	4D4	4.03	.20	10.40	17.50	169.00		1.65	2	13	15							
23.3	25.3	11325	2.0	1.7	4D41	4.64	.03	3.30	8.70	54.00		.75	4	30	34							
25.3	28.2	11326	2.9	2.5	4E4	4.04	.11	6.70	15.70	121.00		1.23	2	13	16							
28.2	30.4	11327	2.2	2.1	4E4	4.80	.10	6.00	12.90	120.00		.89	3	24	28							
30.4	32.8	11328	2.4	2.3	4D4	3.82	.06	9.40	17.50	168.00		1.30	2	11	13							
32.8	34.2	11329	1.4	1.4	4D4	3.96	.06	10.60	20.60	185.00		1.17	2	11	14							
34.2	36.0	11330	1.8	1.3	4E4	4.28	.06	5.20	12.00	100.00		.69	2	23	25							
36.0	37.0	11331	1.0	.6	4D12	3.64	.03	3.00	7.20	48.00		.48	2	16	19							
37.0	38.5	11332	1.5	1.5	4E4	4.88	.15	5.30	8.90	70.00	67.00	1.92	2	34	37							
38.5	39.7	11333	1.2	1.2	4E4	4.83	.20	6.10	9.80	92.00		1.10	2	32	34							
39.7	40.7	11334	1.0	1.0	4CD4	3.68	.09	3.80	7.70	77.00		.69	1	16	17							
40.7	42.1	11335	1.4	1.2	4E4	4.42	.07	5.10	10.70	88.00		1.10	1	25	26							
42.1	44.7	11336	2.6	2.6	5B6	3.04	.06	.56	1.56	8.00		.21	1	4	6							
52.2	54.2	11337	2.0	.0	4E4	4.06	.18	6.40	11.10	114.00		1.65	1	20	22							
54.2	56.2	11338	2.0	.0	4E4	4.63	.13	5.30	9.90	97.00		1.58	2	28	31							
56.2	58.2	11339	2.0	.0	4E4	4.98	.22	5.10	7.60	91.00		1.51	2	33	36							
58.2	60.2	11340	2.0	.0	4E4	4.94	.15	5.80	8.30	98.00		1.44	2	33	36							
60.2	61.2	11341	1.0	.0	4E4	4.86	.22	6.50	12.00	125.00		5.62	3	29	32							
61.2	61.9	11342	.7	.0	4A4	3.33	.08	5.60	8.50	82.00	77.00	1.23	1	7	9							
61.9	64.0	11343	2.1	.0	4A0	3.31	.11	1.40	2.32	31.00		.75	1	14	15							
64.0	66.0	11344	2.0	.0	4A0	3.19	.10	1.68	3.00	34.00		1.03	1	11	13							
66.0	68.0	11345	2.0	.0	4A0	3.29	.14	.37	1.02	20.00		.69	1	15	17							
68.0	70.0	11346	2.0	.0	4A0	3.20	.12	.54	.86	21.00		.41	1	12	14							
70.0	72.4	11347	2.4	.0	4A0	3.10	.10	.40	.86	16.00		.31	1	10	11							
72.4	75.0	11348	2.6	.0	4E4	3.91	.18	5.30	10.60	100.00		1.65	2	19	22							
75.0	77.0	11349	2.0	1.5	4E4	4.78	.17	3.10	7.10	52.00		1.37	4	31	35							
77.0	78.5	11350	1.5	1.5	4E4	4.76	.10	2.40	4.90	43.00		1.51	3	34	37							
78.5	80.5	11351	2.0	2.0	4D4	4.04	.10	6.10	17.50	114.00		1.23	3	14	17							
80.5	83.4	11352	2.9	2.9	4D4	3.99	.06	10.20	20.60	182.00	170.00	1.65	2	11	14							
83.4	84.7	11353	1.3	1.3	4D41	3.41	.01	1.90	6.50	27.00		.55	3	10	13							
84.7	86.6	11354	1.9	1.9	4D4	3.79	.07	4.50	13.70	116.00		1.03	2	14	16							
86.6	89.0	11355	2.4	2.4	4D4	3.69	.14	7.90	18.20	138.00		1.37	2	8	11							
89.0	90.7	11356	1.7	1.4	4D4	3.71	.03	8.60	20.50	140.00		1.03	3	6	10							
90.7	92.3	11357	1.6	1.6	4A0	3.47	.25	3.30	2.40	52.00		1.65	1	16	17							

DDH: FAGU126

-----DEPTHS-----		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAC %	HG %	MN %	AS %	BA %	S.G. W.R.
.0	3.7	07893	3.7	1.4	4A1	2.89	.04	1.37	1.73	25.00		.55	1	3	4						
3.7	6.1	07894	2.4	1.6	4A14	2.95	.05	1.62	4.20	29.99		.55		3	4						
6.1	7.6	07895	1.5	1.5	4D0	3.14	.11	2.70	3.00	47.00		1.16		8	9						
7.6	9.7	07896	2.1	1.6	4C0	2.87	.07	1.53	2.70	27.99		6.16		3	4						
9.7	12.2	07897	2.5	2.5	4A14	2.98	.08	1.62	4.20	36.00		.89	1	3	4						
12.2	15.2	07898	3.0	2.9	4A14	2.97	.07	2.89	5.79	44.00		.62	1	2	3						
15.2	17.4	07899	2.2	2.0	4A14	2.93	.05	1.69	4.90	34.00		3.02		1	2						
17.4	19.4	07900	2.0	2.0	4A14	2.79	.02	1.81	4.70	33.00	33.00	.34			1						
19.4	20.9	08001	1.5	1.5	4A41	3.12	.05	3.79	5.70	61.99		1.30	1	6	7						
20.9	22.9	08002	2.0	1.9	4AE4	3.62	.10	8.40	4.79	104.00		2.25		15	16						
22.9	24.4	08003	1.5	1.5	4AE4	3.41	.08	5.00	3.29	55.00		2.06	1	14	15						
24.4	25.9	08004	1.5	1.5	4AE4	3.60	.17	3.60	3.20	40.00		1.91	1	20	21						
25.9	27.4	08005	1.5	1.5	4AE4	3.54	.16	7.29	4.09	95.00		2.33	1	14	15						
27.4	28.3	08006	.9	.6	4AE4	3.29	.10	5.59	8.40	83.00		1.85	1	9	10						
28.3	30.0	08007	1.7	1.7	4D4	4.25	.05	5.09	9.69	83.00		1.58	1	7	9						
30.0	31.9	08008	1.9	1.9	4A4	3.27	.05	4.90	10.19	80.00		1.70	1	7	8						
31.9	33.5	08009	1.6	1.6	4D45	3.22	.05	3.89	8.19	75.00		1.16	1	8	9						
33.5	35.5	08010	2.0	1.9	4D45	3.12	.05	4.20	8.40	75.00	73.00	.81	1	8	9						
35.5	37.2	08011	1.7	1.7	4D45	3.25	.02	4.29	7.59	78.00		1.58	1	8	10						
37.2	38.5	08012	1.3	1.3	4D45	3.25	.02	4.29	6.99	74.00		1.10	1	8	10						
38.5	40.3	08013	1.8	1.8	4D45	3.31	.05	5.09	8.90	81.00		1.43	1	8	9						
40.3	42.1	08014	1.8	1.8	4AE4	3.49	.05	4.59	10.09	85.00		2.25	1	12	14						
42.1	43.9	08015	1.8	1.7	4AE4	3.43	.05	5.29	9.09	90.00		2.12	1	11	12						
43.9	45.7	08016	1.8	1.8	4D45	3.33	.02	5.00	8.10	85.00		1.51	1	10	11						
45.7	47.2	08017	1.5	1.5	4D50	3.35	.04	3.29	5.09	61.99		1.78	1	3	4						
47.2	48.8	08018	1.6	1.5	4D45	3.43	.04	5.20	10.50	84.00		1.98	1	9	11						
48.8	50.7	08019	1.9	1.9	4D45	3.60	.04	6.79	8.90	96.00		1.98	1	13	14						
50.7	51.4	08020	.7	.7	4A14	3.29	.11	3.29	2.79	48.00	44.00	1.30	1	15	17						
51.4	53.3	08021	1.9	1.9	4L1	2.98	.01	.55	2.19	6.00		.34	2	1	4						
53.3	54.9	08022	1.6	1.5	4L1	2.95	.02	.53	1.53	9.00		.81	1	2	4						
54.9	56.8	08023	1.9	1.9	4L1	3.00	.05	.57	1.95	7.99		.75	1	4	6						
56.8	58.3	08024	1.5	1.5	4A1	2.99	.04	1.41	3.10	20.00		1.10	1	4	5						
74.2	76.2	08025	2.0	2.0	4A13	3.00	.07	.56	1.15	9.00		.75	1	7	8						
76.2	78.3	08026	2.1	2.1	4A13	3.27	.13	.83	2.08	18.00		1.03	1	13	15						
78.3	79.9	08027	1.6	1.6	4E46	4.61	.16	4.79	9.00	88.00		1.70	1	26	28						
79.9	81.1	08028	1.2	1.2	4E4	4.37	.11	3.99	7.59	74.00		1.37	1	27	29						
81.1	83.0	08029	1.9	1.8	4A0	3.14	.08	1.64	2.79	26.00		.95		9	10						
83.0	85.3	08030	2.3	2.3	4A4	2.91	.04	2.97	5.40	37.00	40.00	.55	1	4	5						
85.3	87.5	08031	2.2	2.2	4A0	2.18	.14	.44	.61	11.00		.40	5	9	14						
87.5	89.9	08032	2.4	2.2	4A4	3.29	.05	3.00	5.20	43.00		.75	3	10	13						
89.9	91.4	08033	1.5	1.5	4E4	4.29	.11	5.40	9.30	94.00		1.37	1	26	27						
91.4	93.0	08034	1.6	1.5	4E4	3.87	.07	3.60	5.00	54.00		.75	1	20	22						
93.0	94.5	08035	1.5	1.5	4E0	4.55	.26	1.33	.91	21.00		1.37	1	37	39						
94.5	96.2	08036	1.7	1.7	4E4	4.86	.28	2.70	3.70	49.00		1.70	1	39	40						
96.2	97.5	08037	1.3	1.3	4G4	4.63	.14	5.40	9.90	114.99		1.51		17	18						
97.5	98.8	08038	1.3	1.1	4E4	4.55	.08	3.39	11.40	65.00		1.03		26	27						
98.8	100.3	08039	1.5	1.5	4G0	4.67	.11	2.29	6.00	31.99		1.16		16	17						
100.3	101.8	08040	1.5	1.5	4G4	4.46	.16	6.20	9.80	114.99	110.00	1.58		23	24						
101.8	103.6	08041	1.8	1.6	4E4	4.57	.17	6.09	7.09	36.00		2.04	1	31	33						
103.6	105.2	08042	1.6	1.6	4E4	4.42	.17	4.20	3.29	75.00		1.64	1	33	34						
105.2	107.5	08043	2.3	2.3	4E4	4.78	.20	3.39	2.60	45.00		2.54	1	39	40						

DDH: FAGU126

						-----ASSAYS-----															
DEPTHS	SAMPLE	INT.	REC.	ROCK	S.G.	CU	PB	ZN	AG(AA)	AG(FA)	AU(FA)	PO	PY	TOT	BAC	HG	MN	AS	BA	S.G.	
FROM	TO	NO.		UNIT	PULP	%	%	%	G/MT	G/MT	G/MT	%	%	FE	%	%	%	%	%	W.R.	
118.6	119.7	08044	1.1	1.1	4E#4	4.13	.07	2.39	3.79	34.00		.95	2	21	23						
119.7	120.4	08045	.7	.6	3G0	3.12	.34	.99	1.12	25.00		.68	4	4	9						
120.4	121.9	08046	1.5	1.5	4E4	4.24	.11	4.29	5.09	83.00		1.16	9	24	33						
121.9	123.2	08047	1.3	1.3	4E4	4.67	.13	3.99	7.20	70.00		1.85		23	24						
123.2	125.4	08048	2.2	2.0	4G0	4.09	.13	3.20	5.29	44.00		1.10	3	20	24						
125.4	127.3	08049	1.9	1.9	4E4	4.67	.20	3.99	7.59	73.00		1.98	1	22	24						
127.3	129.0	08050	1.7	1.7	4E4	4.42	.23	3.39	5.40	49.00	47.00	1.30	1	33	34						
129.0	129.5	08051	.5	.5	4C0	3.83	.17	1.02	2.12	28.99		1.58		32	33						
129.5	130.2	08052	.7	.7	4A4	3.54	.11	5.00	9.44	75.00		2.81	1	26	27						
130.2	131.3	08053	1.1	1.0	4C0	3.74	.40	1.24	2.79	34.00		1.78	2	12	14						
131.3	133.1	08054	1.8	1.7	4C0	3.56	.24	.40	1.24	27.00		1.03	2	23	25						
133.1	134.6	08055	1.5	1.5	4A30	3.56	.29	.05	.57	73.00		.89	1	22	23						
134.6	136.1	08056	1.5	1.5	4C0	3.49	.23	.16	.44	13.00		1.23	1	20	22						
136.1	137.0	08057	.9	.9	4C0	3.56	.35	1.41	2.08	31.99		1.51	1	17	19						



DDH: FAGU128

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PC %	PY %	TOT FE	BAO %	HG %	MN %	AS %	BA %
.0	3.6	07374	3.6	.4	4A0	3.02	.04	1.91	2.20	27.00		.81	1	6	8					
3.6	5.0	07375	1.4	1.4	4A4	3.24	.08	2.95	4.29	55.00		1.10		10	11					
5.0	6.5	07376	1.5	1.5	4A4	3.41	.08	2.95	5.67	55.00		.89		14	15					
6.5	8.0	07377	1.5	1.5	4A4	3.10	.05	1.91	3.99	31.99		.68		8	9					
8.0	9.5	07378	1.5	1.5	4A4	3.04	.07	2.18	3.79	37.00		.89		6	7					
9.5	11.1	07379	1.6	1.6	4A4	3.37	.05	2.52	4.09	40.00		.89		4	5					
11.1	13.3	07380	2.2	2.2	4A0	2.89	.02	1.87	3.10	25.00	27.99	.55		3	4					
13.3	14.8	07381	1.5	1.2	4A14	2.95	.02	1.88	3.99	26.00		.81		3	4					
14.8	16.7	07382	1.9	1.9	4A14	3.20	.02	1.39	4.40	29.99		.81		10	11					
16.7	18.7	07383	2.0	1.5	4D4\$	3.79	.05	7.78	9.09	127.99		1.64	1	17	18					
18.7	19.6	07384	.9	.9	4D0	3.31	.05	4.53	3.79	53.00		1.37	1	11	12					
24.5	26.5	07385	2.0	1.9	4A14	3.66	.16	2.75	3.60	48.00		1.78	18	1	20					
67.5	67.8	07386	.3	.3	4A4		.05	4.63	8.40	92.00										
69.7	70.6	07387	.9	.9	4D4	3.64	.10	6.41	10.19	97.00		1.51	1	15	16					
70.6	72.0	07388	1.4	1.4	4A14	3.79	.11	4.32	4.50	76.00		2.19	1	21	22					
72.0	74.7	07389	2.7	2.5	4D4@	3.79	.10	7.25	9.59	103.00		2.06	1	16	18					
74.7	76.3	07390	1.6	1.6	4D4	3.68	.08	6.21	10.09	90.00		1.85	1	14	16					
76.3	77.6	07391	1.3	1.3	4D4@	3.54	.08	5.46	9.90	87.00		1.64	1	12	14					
77.6	78.9	07392	1.3	1.0	5A0	3.04	.02	3.06	3.70	48.00		.40	2	4	6					
79.4	81.6	07393	2.2	2.2	4GE4	4.63	.08	5.25	10.69	92.00		1.37		19	20					
81.6	82.5	07394	.9	.8	4G4@	4.63	.08	5.46	10.40	100.00		1.30	1	26	27					
82.5	83.8	07395	1.3	1.3	4G4	4.66	.11	6.83	10.50	102.00	104.00	1.64		18	19					

DDH: FAGU129

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														S.G. W.R.	
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAC %	HG %	MN %	AS %	BA %		
5.0	7.0	07536	2.0	2.0	4A14	2.97	.02	3.83	4.90	63.99			.75	1	2	3						
7.0	9.0	07537	2.0	1.5	4A14	3.00	.02	4.59	5.70	79.00			.55	1	2	3						
9.0	10.9	07538	1.9	1.8	4A14	2.89	.02	2.99	2.70	44.00			.68	1	1	3						
10.9	12.5	07539	1.6	1.0	4L14	2.91	.02	2.02	1.74	35.00			1.30		4	5						
12.5	14.1	07540	1.6	1.6	4L14	2.91	.05	1.02	.63	22.00	17.00		.89		6	7						
14.1	15.8	07541	1.7	1.4	4L14	2.95	.05	1.57	1.28	28.99			1.16		6	6						
15.8	17.3	07542	1.5	.4	4L14	3.00	.07	2.95	1.23	43.00			.81		5	6						
17.3	19.3	07543	2.0	.9	4L14	2.89	.02	2.29	2.39	27.99			.89		6	6						
19.3	21.3	07544	2.0	1.6	4L14	2.89	.02	2.41	1.58	27.99			.68		5	6						
21.3	23.4	07545	2.1	2.1	4L14	2.87	.02	1.65	2.02	26.00			.62		2	2						
23.4	25.7	07546	2.3	2.3	4A1	2.87	.02	1.26	1.86	20.00			.47	1	1	2						
25.7	27.0	07547	1.3	1.3	4A1	2.95	.01	.81	1.67	13.99			.27	2	3	5						
53.9	55.9	07548	2.0	2.0	4L1		.05	.48	.84	11.00												
55.9	58.5	07549	2.6	2.4	4L1		.07	1.04	1.91	21.00												
68.3	70.3	07550	2.0	1.8	4A1	2.97	.08	.17	.54	6.99	5.00		.55	1	9	11						
70.3	72.2	07551	1.9	1.5	4A1	3.06	.08	1.29	2.89	27.00			.68	1	7	8						
72.2	73.6	07552	1.4	1.4	4A13	3.14	.07	1.36	2.20	27.00			.81	1	14	16						
73.6	74.9	07553	1.3	1.3	4A13	3.58	.17	.47	.80	22.00			.95	2	22	24						
74.9	75.6	07554	.7	.7	4E#	4.42	.34	3.70	5.29	99.00			1.85	1	30	32						
75.6	77.3	07555	1.7	1.2	4E#4	4.42	.05	2.60	3.00	46.00			1.10	2	37	39						
77.3	79.1	07556	1.8	.8	4E#4	4.94	.14	4.13	7.40	53.00			1.58	3	36	40						
79.1	80.9	07557	1.8	.7	4E#4	4.69	.02	2.20	5.90	41.00			.68	4	20	24						
80.9	82.3	07558	1.4	1.2	4G0	4.73	.02	1.19	4.59	26.00			.55		15	15						
82.3	83.5	07559	1.2	1.2	4G0	4.86	.05	3.10	6.09	48.00			.95	1	20	21						
83.5	84.1	07560	.6	.5	4GK0	4.12	.13	2.70	6.00	48.00	5.00		.95	1	25	26						
84.1	85.1	07561	1.0	.7	4G4	4.63	.16	3.70	7.49	75.00			1.85	1	21	22						
85.1	87.2	07562	2.1	2.1	4E#4	4.70	.19	4.41	6.59	72.00			1.43	2	33	35						
89.2	90.6	07563	1.4	.9	4G0	4.61	.02	2.25	5.20	45.00			1.16		11	11						
90.6	92.0	07564	1.4	.5	4G0	4.40	.04	2.70	3.79	63.99			.95		22	23						
121.3	121.9	07565	.6	.6	4HD	3.76	.14	5.70	8.69	87.00			1.10	4	4	8						
121.9	122.6	07566	.7	.6	4D4	3.95	.07	12.50	18.30	200.00			2.39	5	8	14						
122.6	123.0	07567	.4	.4	4E#4	4.55	.28	2.79	3.99	44.00			2.12	1	35	37						
123.0	124.3	07568	1.3	1.3	4E4	4.67	.26	5.20	8.40	76.00			1.98	1	33	35						
124.3	125.6	07569	1.3	1.3	4E4	4.37	.16	3.99	7.70	74.00			1.78	1	30	32						
125.6	127.3	07570	1.7	1.7	4E#4	4.13	.33	1.65	3.39	38.00	39.00		.40	2	32	34						
127.3	129.0	07571	1.7	1.7	4E#	4.38	.42	1.71	2.39	44.00			1.78	3	34	38						
129.0	129.9	07572	.9	.9	4E#	4.38	.53	1.40	2.29	40.00			2.19	2	34	37						
129.9	131.3	07573	1.4	1.4	4E4	4.98	.34	4.29	6.20	78.00			2.19	3	30	34						
131.3	132.8	07574	1.5	1.4	4E0	3.72	.27	1.47	3.00	34.00			1.70	2	22	25						
132.8	133.6	07575	.8	.8	4D0	3.52	.13	3.70	3.99	51.00			3.02	2	17	19						
133.6	134.6	07576	1.0	1.0	4D4	3.70	.08	8.59	13.00	113.99			2.06	2	12	15						

DDH: FAGU130

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														S.G. W.R.	
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAC %	HG %	MN %	AS %	BA %		
.0	2.2	07503	2.2	1.0	4L14	2.98	.04	2.79	1.60	45.00		.68	1	3	4							
8.5	10.0	07504	1.5	1.5	4A14	3.06	.04	1.81	3.89	36.00		.68	2	6	8							
10.0	11.0	07505	1.0	1.0	4A14	3.10	.04	2.99	5.09	47.00		1.03	1	6	8							
18.2	19.5	07506	1.3	1.3	4D0	3.12	.02	2.83	5.59	43.00		1.37	1	6	7							
19.5	21.0	07507	1.5	1.5	4A14	3.02	.02	3.99	7.70	68.00		1.03	1	9	10							
21.0	22.9	07508	1.9	1.7	4A14	3.33	.08	3.79	7.29	62.99		1.37	1	11	12							
22.9	24.3	07509	1.4	1.4	4A14	3.12	.08	2.52	5.00	47.00		1.03	1	7	8							
24.3	24.9	07510	.6	.6	5C*3	3.02	.01	.08	.13	1.99		.95	4		5							
24.9	26.9	07511	2.0	2.0	4L14	3.02	.02	2.33	2.87	35.00		.81	1	2	3							
26.9	28.1	07512	1.2	1.2	4L14	3.10	.04	4.59	3.70	74.00		1.16		6	6							
28.1	29.5	07513	1.4	1.4	4L14	3.02	.02	3.00	3.60	49.00		.95		4	5							
29.5	31.0	07514	1.5	1.5	4L14	3.00	.04	1.49	2.70	27.00		.95		5	6							
31.0	32.6	07515	1.6	1.5	4L14	3.02	.05	1.34	2.02	22.00		1.70		6	7							
32.6	34.2	07516	1.6	1.6	4L0	3.41	.02	1.39	1.46	19.00		.47		2	3							
34.2	36.0	07517	1.8	1.7	4A0	3.14	.02	1.73	3.10	39.00		.81		8	9							
36.0	37.6	07518	1.6	1.5	4AE	3.41	.08	4.50	8.69	80.00	72.00	1.23	2	13	15							

DDH: FAGU131

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													S.G. W.R.		
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAO %	HG %	MN %	AS %		BA %	
.5	1.5	11096	1.0	.5	4G4	4.67	.09	3.80	6.70	80.00		1.03		23	23							
1.5	3.2	11097	1.7	1.0	4G4	4.75	.11	4.70	9.40	89.00		.96	1	19	20							
3.2	4.6	11098	1.4	1.4	4G4	4.51	.08	4.40	8.40	105.00		.82		11	12							
4.6	5.5	11099	.9	.9	4E4	4.64	.22	5.70	10.50	109.00		1.23	3	28	32							
15.3	16.8	11100	1.5	1.0	4G4	4.20	.17	5.10	7.50	89.00		1.58	2	21	23							

DDH: FAGU132

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP.	CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AL(FA) G/MT	-----ASSAYS-----						S.G. W.R.	
FROM	TO												PO %	PY %	TOT FE	BAO %	HG %	MN %		AS %
15.5	16.2	07622	.7	.7	4HE4	.02	1.79	10.19	90.00											
43.5	44.8	07623	1.3	1.3	4A0	.02	.68	3.49	33.00											
52.3	53.5	07624	1.2	1.2	4A4	3.16	.02	3.10	7.09	58.99		.95	1	7	9					
62.1	64.7	07625	2.6	2.6	4D4	3.54	.13	3.89	6.50	76.00		1.64	1	14	16					
64.7	66.6	07626	1.9	1.9	4AC0	3.25	.04	1.35	2.29	24.00		1.10	1	11	12					
66.6	69.3	07627	2.7	2.7	5B62	2.91	.02	1.09	1.31	13.00		.55	2	2	4					
69.3	70.6	07628	1.3	1.3	5A61	2.87	.02	1.05	1.37	13.00		.89		2	3					
70.6	72.3	07629	1.7	1.7	4D4	3.43	.10	3.89	6.59	72.00		1.37	1	12	14					
72.3	74.3	07630	2.0	1.9	5A61	3.10	.04	1.20	2.02	29.99		.07		8	9					
74.3	77.3	07631	3.0	2.7	5A61	2.93	.02	.38	1.01	10.00		.27	1	2	3					
83.6	84.9	07632	1.3	1.3	4A4	3.02	.05	2.50	3.99	48.00		.95	3	5	8					
84.9	86.6	07633	1.7	1.0	5D4a	3.25	.08	1.31	3.99	33.00		.47	7	7	14					
86.6	87.8	07634	1.2	1.2	4D07	3.06	.05	3.00	6.50	60.99		.81	3	4	7					
87.8	89.0	07635	1.2	1.2	5D4a	3.25	.02	.71	1.66	14.99		.27	9	7	17					
89.0	91.0	07636	2.0	2.0	4D0	3.14	.02	3.20	4.90	61.99		.40	3	6	9					
91.0	93.0	07637	2.0	1.9	4D0	2.95	.04	2.39	3.49	42.00		.75	3	3	6					
93.0	95.0	07638	2.0	2.0	4D0	2.89	.02	1.64	3.39	29.99		.40	2	2	5					
95.0	97.0	07639	2.0	2.0	4D0	3.06	.05	2.79	3.79	47.00		.68	3	5	8					
97.0	99.0	07640	2.0	2.0	4C0	2.89	.02	1.99	2.70	39.00	35.00	.89	2	3	5					
99.0	100.4	07641	1.4	1.0	4D0	3.02	.05	3.00	4.90	54.00		.89	2	4	6					
100.4	101.7	07642	1.3	1.3	4AD	2.93	.04	2.60	2.79	47.00		.75	1	3	5					
101.7	103.9	07643	2.2	2.2	4AD	2.99	.02	1.72	4.59	37.00		.47	2	4	6					
103.9	105.2	07644	1.3	1.0	5AD	2.95	.02	.28	1.43	6.99		.27	4	2	6					
105.2	108.8	07645	3.6	2.0	5D4L	2.95	.02	1.36	2.79	29.99		1.16	3	2	6					

DDH: FAGU133

					-----ASSAYS-----																
DEPTHS	SAMPLE	INT.	REC.	ROCK	S.G.	CU	PB	ZN	AG(AA)	AG(FA)	AU(FA)	PO	PY	TOT	BAO	HG	MN	AS	BA	S.G.	
FROM	TO	NO.		UNIT	PULP	%	%	%	G/MT	G/MT	G/MT	%	%	FE	%	%	%	%	%	W.R.	
.0	3.0	09898	3.0	1.3	4G4	4.88	.19	4.60	8.30	85.00				1.23	2	23	25				
3.0	5.0	09899	2.0	2.0	4G4	5.03	.07	4.30	8.80	87.00				.62	1	12	13				
5.0	7.0	09900	2.0	2.0	4G4	4.84	.11	3.90	7.90	73.00				.48	1	16	18				
7.0	8.5	11101	1.5	1.5	4G4	5.19	.08	4.70	9.10	84.00				.96		14	15				
8.5	10.2	11102	1.7	1.7	4E4	4.94	.14	5.90	9.70	116.00	100.00			1.51	2	31	33				
10.2	12.1	11103	1.9	1.9	4G4	4.64	.15	5.30	8.90	94.00				.96		29	30				
12.1	14.5	11104	2.4	2.4	4E4	5.13	.14	2.30	4.40	70.00				.75		34	34				
14.5	16.3	11105	1.8	1.8	4D4	4.64	.08	3.40	7.50	63.00				.75		22	23				
16.3	18.2	11106	1.9	1.9	4E4	4.50	.26	4.80	6.70	113.00				1.44	1	29	30				
47.3	49.3	11107	2.0	2.0	4D4	3.56	.08	10.00	19.00	152.00				1.51	2	7	9				
49.3	51.3	11108	2.0	2.0	4D4	3.74	.06	9.20	17.70	151.00				1.44	3	8	12				
51.3	53.1	11109	1.8	1.8	4D4	3.57	.08	8.20	14.60	131.00				1.58	3	8	11				
54.5	56.0	11110	1.5	1.5	4D4	3.54	.26	5.00	5.70	89.00				2.13	1	18	20				
56.0	57.3	11111	1.3	1.3	4E4	4.17	.23	2.30	4.90	45.00				1.17	2	30	33				
57.3	59.2	11112	1.9	1.9	4A4	3.83	.08	4.10	8.60	68.00	70.00			1.30	2	15	18				
59.2	61.2	11113	2.0	1.9	4A0	3.41	.21	1.00	2.50	23.00				.75	1	18	19				
61.2	63.3	11114	2.1	2.1	4A0	3.18	.16	.17	1.12	12.00				.41	1	13	14				
63.3	64.0	11115	.7	.5	4E0	3.55	.13	1.66	2.50	27.00				.21	6	13	20				
64.0	67.1	11116	3.1	2.3	4A0	3.23	.43	.14	.87	19.00				.41	1	13	14				
67.1	70.0	11117	2.9	2.3	4A0		.20	.18	.80	16.00											
93.0	96.3	11118	3.3	3.0	4L4	4.07	.48	.26	2.60	23.00				.48	2	33	35				
114.3	115.8	11119	1.5	1.5	4G4	4.12	.18	6.20	8.40	106.00				1.51	2	12	14				
115.8	117.6	11120	1.8	1.8	4E4	5.56	.21	2.80	3.10	41.00				.75	5	26	31				

DDH: FAGU134

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														S.G. W.R.
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAC %	HG %	MN %	AS %	BA %	
5.9	6.7	07396	.8	.8	4L4	2.89	.10	.67	1.44	12.00		.40	2	3	5						
6.7	8.0	07397	1.3	1.1	5A19	2.97	.02	1.12	.69	12.00		.20	3	3	6						
19.3	20.6	07398	1.3	1.3	4L0	3.12	.02	.14	.44	.99		.27	4	1	5						
29.0	29.8	07399	.8	.8	4D0	3.33	.04	4.84	2.89	84.00		.95	1	4	6						
29.8	31.8	07400	2.0	2.0	4A1	3.04	.05	2.64	1.16	37.00		1.03		3	4						
31.8	33.9	08101	2.1	2.1	4A1	3.00	.07	2.29	1.13	29.99		1.03		3	4						
33.9	36.3	08102	2.4	2.4	4A1	2.95	.07	1.70	1.08	18.00		.89		3	4						
36.3	38.7	08103	2.4	2.4	4A1	2.95	.08	1.36	.70	13.99		.89		4	5						
38.7	41.0	08104	2.3	2.3	4A1	2.97	.05	.93	.72	18.00		1.43		4	5						
41.0	42.0	08105	1.0	1.0	4A1	3.02	.02	3.20	1.26	33.00		2.81		3	4						
42.0	44.1	08106	2.1	2.1	4A1	3.00	.02	2.39	2.39	25.00		.62	1	2	3						
44.1	45.8	08107	1.7	1.6	4A1	2.93	.01	.54	.76	6.99		.47	1	1	3						
45.8	46.6	08108	.8	.8	4A17	2.93	.02	.32	.40	3.99		.47	2	1	4						
46.6	48.3	08109	1.7	1.7	4A17	2.95	.01	.64	.76	10.00		.47	3	1	4						
48.3	49.6	08110	1.3	1.3	4A17	2.81	.01	.77	1.44	12.00	11.00	.40	2		3						
49.6	51.6	08111	2.0	2.0	4A17	2.91	.01	.85	1.32	12.00		.40	1		2						
51.6	53.6	08112	2.0	2.0	4A17	2.91		1.28	1.63	20.00		.34	1		2						
53.6	55.1	08113	1.5	1.5	4A17	2.89	.02	.93	1.42	12.00		.03	1	1	2						
55.1	57.0	08114	1.9	1.9	4A1	2.95	.08	1.53	2.20	28.99		1.78	1	21	23						
57.0	58.5	08115	1.5	1.5	4A1	3.39	.05	1.56	1.99	28.99		1.98	1	15	16						
58.5	60.0	08116	1.5	1.5	4A14	3.56	.11	4.90	5.09	71.00		2.06	1	15	17						
60.0	62.1	08117	2.1	1.8	4D45	3.27	.05	3.89	6.79	60.99		1.43	1	9	11						
62.1	63.4	08118	1.3	1.1	4A14	3.64	.14	4.40	6.99	74.00		2.06	1	16	18						
63.4	64.7	08119	1.3	1.3	4A14	3.43	.05	3.70	6.29	52.00		1.30	1	13	15						
64.7	65.3	08120	.6	.6	4C0	3.87	.02	.32	1.11	13.99		1.91	2	27	29						
69.6	71.4	08121	1.8	1.8	4A0		.02	.76	2.39	12.00											
85.3	86.8	08122	1.5	.1	4A4	2.99	.10	6.70	9.00	103.00		1.98	2	15	17						
88.1	91.4	08123	3.3	1.0	4A1	3.41	.22	1.76	1.61	31.99	33.00	.34	13	10	23						



DDH: FAGU136

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAC %	HG %	MN %	AS %	BA %
31.0	32.0	11151	1.0	.8	4L4	4.24	.22	2.90	2.30	41.00		.48	7	16	23					
32.0	34.6	11152	2.6	1.8	4G4	4.72	.09	5.30	5.80	80.00		.69	1	23	24					
39.1	41.1	11153	2.0	1.3	4G4	4.94	.20	2.70	2.04	57.00	57.00	.96	2	33	36					
41.1	44.2	11154	3.1	1.6	4E4	4.83	.23	4.40	3.70	71.00		.89	3	35	38					
44.2	46.2	11155	2.0	1.0	4G4	4.67	.08	6.30	7.70	98.00		.55	2	13	16					
46.2	48.2	11156	2.0	1.0	4G4	5.01	.10	6.60	6.80	110.00		.41	3	12	16					
48.2	50.2	11157	2.0	1.8	4G4	4.86	.06	7.30	7.60	125.00		.41	2	10	13					
50.2	51.7	11158	1.5	1.5	4G4	4.64	.12	5.60	6.60	90.00		.48	4	17	21					
51.7	53.3	11159	1.6	1.4	4G4	4.54	.11	6.20	6.60	101.00		.62	1	19	21					
53.3	54.7	11160	1.4	1.0	4E4	4.29	.24	4.30	3.60	66.00		.62	5	30	36					
54.7	56.2	11161	1.5	1.0	4L4	3.38	.13	1.57	1.25	30.00		.48	3	12	16					
56.2	58.2	11162	2.0	1.0	4E0	3.98	.18	1.67	1.15	33.00		.69	4	28	33					
58.2	60.2	11163	2.0	.9	4E0	4.35	.53	2.40	1.35	47.00	42.00	1.51	6	24	31					
60.2	61.4	11164	1.2	.8	4E0	3.02	.29	1.49	1.33	44.00		1.03	6	23	30					

DDH: FAGU138

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													S.G. W.R.
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PC %	PY %	TOT FE	BAC %	HG %	MN %	AS %	
2.6	3.9	07312	1.3	1.1	5CD	.02	.88	1.71	15.99											
6.2	7.1	07313	.9	.9	4L14	.02	2.39	2.89	37.00											
31.6	33.3	07314	1.7	1.6	4A1	2.95	.04	2.10	1.51	27.00		.81	2	3	5					
33.3	34.9	07315	1.6	1.6	4A1	2.93	.05	.59	.42	9.00		.95		5	6					
34.9	36.5	07316	1.6	1.5	4A1	3.02	.10	1.32	2.39	22.00		1.10	1	6	7					
36.5	38.0	07317	1.5	1.5	4A14	2.93	.05	1.82	4.29	26.00		1.10	1	3	4					
38.0	39.5	07318	1.5	1.5	4A14	2.95	.05	3.99	2.70	55.99		.89		2	3					
39.5	41.7	07319	2.2	2.2	4A1	2.95	.08	1.58	.69	25.00		1.10	1	5	7					
41.7	43.9	07320	2.2	2.0	4A1	2.85	.05	.23	.44	5.00		.81		3	4					
43.9	46.0	07321	2.1	1.9	4A1	2.93	.02	1.04	.59	14.99		.68		3	4					
46.0	47.7	07322	1.7	1.7	4L04	2.98	.04	4.79	.99	53.00		.95	1	2	3					
47.7	49.4	07323	1.7	1.7	4L04	2.87	.02	1.26	1.33	19.00		.55			1					
49.4	51.1	07324	1.7	1.7	4L04	2.91	.02	1.17	1.90	21.00		.62	1		1					
51.1	52.7	07325	1.6	1.4	4L04	2.89	.02	.59	1.40	9.00		.40	2		2					
52.7	54.8	07326	2.1	2.1	4L14	3.04	.04	2.39	.68	28.99		.81	1	3	5					
54.8	56.8	07327	2.0	2.0	4L14	3.04	.04	1.17	.90	18.00		.75	1	4	5					
56.8	59.1	07328	2.3	2.2	4A1	2.91	.05	1.61	2.60	29.99		.95		3	4					
59.1	61.0	07329	1.9	1.9	4L14	2.95	.05	1.10	1.14	22.00		.89	2	3	5					
61.0	63.0	07330	2.0	2.0	4L1	2.85	.02	.48	.56	7.99	6.99	.40	2	1	4					
76.3	77.0	07331	.7	.7	4L14	2.97	.04	.41	.95	10.00		.20	2	14	16					
77.0	78.9	07332	1.9	1.9	4A1	3.14	.05	1.54	2.70	28.99		.95		10	10					
78.9	80.3	07333	1.4	1.4	4A3	3.54	.13	.07	.16	27.99		1.16	1	21	22					
80.3	81.7	07334	1.4	1.4	4A3	3.14	.05	.80	.68	19.00		4.09		11	12					
81.7	83.5	07335	1.8	1.8	4A14	3.02	.05	2.70	4.29	43.00		.81	1	4	5					
83.5	84.6	07336	1.1	1.1	4A13	3.04	.05	.31	.48	12.00		.75		9	10					
107.7	108.5	07337	.8	.8	4E1	3.31	.02	4.70	9.00	63.99		1.16	1	18	19					
108.5	110.2	07338	1.7	1.7	4A3	3.16	.07	.67	.96	17.00		.75		13	14					
110.2	112.0	07339	1.8	1.8	4A3	3.20	.07	1.02	1.86	21.00		.68		12	12					
112.7	114.0	07340	1.3	.8	4A1	2.79	.05	1.03	2.39	19.00		.40	1	9	11					
114.0	115.8	07341	1.8	1.1	4A1	2.98	.08	.93	1.54	15.99		.55	1	5	6					
115.8	117.6	07342	1.8	1.4	4A1	2.91	.05	1.25	2.16	17.00	14.99	.40	1	3	5					

DDH: FAGU139

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													S.G. W.R.		
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAG %	HG %	MN %	AS %		BA %	
37.9	39.8	11215	1.9	.0	4E4	4.31	.16	7.20	7.30	107.00		.62	3	17	21							
39.8	40.8	11216	1.0	.0	4E0	4.50	.20	1.06	2.50	30.00		2.13	4	36	40							
40.8	42.7	11217	1.9	.0	4E4	4.67	.14	4.00	3.90	66.00		.89	2	32	35							
42.7	44.2	11218	1.5	.0	4E4L			5.97	5.15	83.00												
44.2	45.5	11219	1.3	.0	4G4	3.65	.06	8.70	7.60	113.00		.55	2	21	23							
45.5	46.9	11220	1.4	.0	4L24	3.39	.20	1.26	1.25	20.00		.07	6	15	21							
50.9	53.3	11221	2.4	.0	4L24	3.39	.12	1.43	1.64	17.00		.14	5	12	18							
53.3	56.7	11222	3.4	.0	4L0	3.50	.17	1.32	1.43	26.00		.14	7	14	22							
64.7	66.7	11223	2.0	.0	4L24	3.77	.21	4.90	4.60	71.00		.34	5	17	22							
66.7	68.9	11224	2.2	.0	4L24	3.67	.20	1.51	.84	25.00	30.00	.62	5	16	22							



DDH: FAGU141

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													S.G. W.R.
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAG %	HG %	MN %	AS %	
.0	2.2	09465	2.2	1.1	4A0	.18	.59	1.94	26.00											
2.2	4.5	09466	2.3	2.2	4A0	.26	.37	1.58	25.00											
4.5	5.7	09467	1.2	1.2	4A0	.15	.58	.91	24.00											
5.7	7.6	09468	1.9	1.9	4A0	3.50	.43	1.42	18.00			.62	1	18	20					
7.6	9.2	09469	1.6	1.5	4A4	3.60	4.50	7.00	66.00			1.44	1	16	18					
9.2	10.8	09470	1.6	1.6	4E4	4.81	7.40	12.70	103.00	108.00		3.29	2	28	30					
10.8	12.5	09471	1.7	1.7	4E4	4.65	7.80	12.30	118.00			1.78	1	28	30					
12.5	13.0	09472	.5	.5	4C0	4.07	5.00	6.50	98.00			1.37	2	26	28					
13.0	14.0	09473	1.0	1.0	4E4	4.18	7.00	13.70	96.00			1.37	2	21	23					
14.0	14.4	09474	.4	.4	4G0	4.58	3.70	7.90	68.00			1.78		29	29					
14.4	16.4	09475	2.0	2.0	4D4	4.03	8.30	12.90	130.00			1.92	2	18	20					
16.4	17.6	09476	1.2	1.2	4C3	3.58	1.95	12.80	39.00			1.71	2	21	24					
17.6	18.5	09477	.9	.9	4A4	3.75	7.30	6.40	95.00			2.33	1	18	19					
18.5	19.9	09478	1.4	1.4	4D4	3.80	6.30	6.80	93.00			2.40	2	19	21					
19.9	21.3	09479	1.4	.8	4D4	3.82	6.10	4.60	98.00			2.19	1	20	21					
21.3	22.4	09480	1.1	1.1	4C3	4.39	2.60	1.40	46.00	49.00		2.88	2	29	32					
22.4	24.1	09481	1.7	1.3	4D4	3.61	7.60	10.70	125.00			1.99	3	12	15					
59.8	61.5	09482	1.7	1.7	4GE	4.40	5.20	8.40	93.00			.89	2	23	25					
61.5	62.7	09483	1.2	1.2	4G0	4.48	4.00	8.20	76.00			.62		8	9					

DDH: FAGU142

-----DEPTHS-----						-----ASSAYS-----																
FROM	TO	SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAO %	HG %	MN %	AS %	BA %	S.G. W.R.	
.0	2.1	07232	2.1	1.3	4E4	4.34	.23	9.09	15.90	183.00		4.46	1	18	19							
2.1	3.0	07233	.9	.8	5A9	3.29	.05	1.08	1.79	26.00		.89	1	10	12							
3.0	5.1	07234	2.1	1.8	4E4	4.13	.07	8.59	11.40	163.00		1.91	1	18	19							
5.1	5.5	07235	.4	.4	5A9	3.35	.01	.71	2.04	21.00		.89	1	15	16							
5.5	6.5	07236	1.0	1.0	4C0	3.58	.02	1.79	2.29	38.00		1.37	1	16	18							
6.5	7.2	07237	.7	.7	4A4	3.89	.13	6.20	13.00	142.00		1.91	1	16	17							
7.2	7.9	07238	.7	.7	4D0	3.04	.04	3.00	6.50	53.00	51.00	.68	1	6	8							
7.9	9.4	07239	1.5	1.5	4A41	3.31	.01	4.20	7.49	72.00		.81	1	9	11							
9.4	11.0	07240	1.6	1.6	4A41	3.64	.02	5.00	9.69	96.00		.95	1	14	15							
11.0	11.5	07241	.5	.5	5D4	3.27	.01	1.47	3.39	27.00		.55	2	10	12							
16.2	17.0	07242	.8	.8	4K1		.01	.20	.14	10.00												
21.3	23.4	07243	2.1	2.0	4K1	3.60	.01	.24	.19	13.00		.40	1	18	20							
23.4	24.6	07244	1.2	1.0	4A4	3.41	.02	3.70	8.50	59.99		.68	1	12	13							
24.6	25.1	07245	.5	.5	5D4	3.29	.01	1.93	6.00	33.00		.40	1	9	11							
25.1	25.4	07246	.3	.3	4K4	3.14	.10	7.59	18.00	167.00		2.33	1	14	16							
25.4	27.0	07247	1.6	1.6	4L0	3.29	.01	1.14	2.29	27.99		.34	1	6	7							
27.0	29.0	07248	2.0	2.0	4K7	3.33	.04	.68	1.10	20.00		.34	7	8	15							
29.0	30.6	07249	1.6	1.6	4K7		.02	.52	.57	17.00												
30.6	32.4	07250	1.8	1.8	4K7		.05	.88	1.27	27.99												
32.4	34.4	07251	2.0	1.8	4K7		.04	.36	.32	15.99												
34.4	36.2	07252	1.8	1.8	4K7		.02	.31	.16	13.99												
36.2	38.1	07253	1.9	1.9	4K0		.04	.20	.40	12.00												
38.1	39.6	07254	1.5	1.5	4K0	3.75	.02	.20	.68	12.00		.20	3	20	24							
39.6	39.9	07255	.3	.3	4E4	4.20	.05	9.59	18.80	190.00	184.00	1.16	1	16	17							
39.9	40.3	07256	.4	.4	4D0	3.37	.02	2.14	5.29	45.00		.75		15	16							
40.3	42.5	07257	2.2	2.1	4D4	3.37	.02	4.59	10.40	81.00		1.03	1	9	10							
42.5	44.2	07258	1.7	1.7	4A41	3.27	.02	3.70	9.09	61.99		.89	1	8	9							
44.2	45.9	07259	1.7	1.7	4A41	3.50	.02	5.50	12.40	95.00		.81	1	10	11							
45.9	46.6	07260	.7	.7	4E4	4.61	.08	10.30	24.19	208.00		1.37		18	18							
46.6	48.5	07261	1.9	1.8	4K0	3.97	.01	.68	2.04	20.00		.34	1	24	25							
48.5	50.1	07262	1.6	1.6	4K4	3.97	.01	1.37	4.29	30.99		.55	1	25	26							
50.1	50.9	07263	.8	.8	4E4	4.23	.08	4.90	15.90	119.99		1.30	1	21	22							
50.9	51.4	07264	.5	.5	4A4	3.41	.02	4.40	9.50	81.00		.75		12	13							
51.4	52.9	07265	1.5	1.5	4E4	4.13	.14	5.59	13.59	100.00	94.00	1.78	1	22	23							
52.9	55.1	07266	2.2	2.1	4E4	4.53	.20	7.59	18.30	160.00		1.78	1	21	22							
55.1	55.5	07267	.4	.4	4A4	3.64	.04	7.79	10.00	133.00		1.64	1	13	14							
55.5	55.9	07268	.4	.4	5D4*	3.00	.02	.34	.13	7.99		.34	5	2	7							
55.9	57.9	07269	2.0	2.0	4A0	3.37	.07	2.29	2.60	42.00		1.58	1	15	16							
57.9	59.7	07270	1.8	1.4	4A0	3.52	.02	1.30	3.10	29.99		1.16	2	13	15							
67.0	68.1	07271	1.1	1.1	4A4	3.31	.05	3.10	5.59	59.99		2.74	1	12	13							
68.1	70.2	07272	2.1	2.1	4A4	2.99	.02	1.74	3.70	30.99		.68	1	1	2							
96.3	97.6	07273	1.3	1.3	4C0	3.06	.08	.46	.68	10.00		.40	1	7	9							
97.6	99.5	07274	1.9	1.9	4A0	2.95	.14	1.28	2.10	24.00	23.00	.89	1	7	8							
99.5	101.5	07275	2.0	1.9	4A0	3.14	.11	.42	1.03	15.99		.89	1	12	13							
101.5	103.6	07276	2.1	2.1	4A0	3.16	.13	.67	1.61	20.00		1.10	1	12	13							
103.6	105.3	07277	1.7	1.7	4A0	3.18	.05	2.95	1.71	40.00		1.51		11	12							
105.3	107.5	07278	2.2	2.2	4A0	3.20	.07	1.72	1.20	31.99		1.03		11	12							
107.5	109.4	07279	1.9	1.9	4A0	3.62	.20	.05	.20	26.00		.81	1	24	25							
109.4	111.1	07280	1.7	1.7	4A0		.26	.05	.29	29.99												
111.1	113.1	07281	2.0	2.0	4A0	3.33	.11	.47	.93	21.00		1.03	1	17	18							
113.1	114.7	07282	1.6	1.5	4A4	3.16	.02	2.33	3.18	34.00		1.03	1	10	11							

DDH: FAGU142

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													S.G. W.R.		
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAC %	HG %	MN %	AS %		BA %	
114.7	115.3	07283	1.1	1.1	4A0	3.37	.10	.05	.20	13.00		.81	1	18	19							
115.8	117.0	07284	1.2	1.2	4A0	3.56	.16	.10	.23	14.99		.68	1	23	24							
117.0	119.1	07285	2.1	2.1	4G4	4.69	.14	4.70	8.10	91.00		2.19	1	28	30							
119.1	121.0	07286	1.9	1.9	4G0	4.40	.02	1.35	3.99	23.00	21.00	.62		17	17							
121.0	123.0	07287	2.0	2.0	4G0	4.67	.17	3.00	5.40	63.99		1.30		28	28							
123.0	125.0	07288	2.0	1.9	4E4	4.58	.17	5.70	11.00	100.00		1.43	1	26	28							
125.0	127.5	07289	2.5	2.2	4E46	4.12	.14	3.79	7.79	70.00		1.51	1	23	24							
127.5	128.9	07290	1.4	1.2	4E4	3.66	.04	3.29	8.10	65.00		1.03	5	9	14							





DDH: FAGU144

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----															
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAC %	HG %	MN %	AS %	BA %	S.G. W.R.	
57.3	57.9	08431	.6	.6	4B4	2.93	.01	2.60	5.90	42.00		.68	2	1	3							
57.9	59.4	08432	1.5	1.5	4A34	3.27	.05	3.60	7.79	60.99		.81	2	28	31							
59.4	61.0	08433	1.6	1.2	4A34	3.49	.07	4.09	6.09	72.00	74.00	1.91	2	15	17							
61.0	61.2	08434	.2	.2	4H14	3.93	.05	5.70	7.29	96.00		1.10	21	8	30							
64.1	65.9	08435	1.8	1.8	4A14	2.98	.02	1.88	3.49	31.99		.95	1	8	10							

DDH: FAGU145

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													S.G. W.R.
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PG %	PY %	TOT FE	BAC %	HG %	MN %	AS %	
2.3	4.1	09637	1.8	1.4	4A3	.19	.10	.94	8.00											
4.1	5.9	09638	1.8	1.8	4A3	.12	.03	1.25	6.00											
5.9	7.7	09639	1.8	1.8	4A3	.18	.09	.53	8.00											
7.7	9.5	09640	1.8	1.8	4A3	.10	.30	1.08	13.00											
9.5	10.0	09641	.5	.5	4A3	.16	.09	1.45	7.00											
10.0	12.1	09642	2.1	2.1	4A13	.21	.15	.69	11.00											
12.1	14.2	09643	2.1	2.1	4A13	.40	.25	.60	21.00											
14.2	16.3	09644	2.1	2.1	4A13	.20	.06	.42	6.00											
16.3	18.5	09645	2.2	2.2	4A13	.11	.06	.44	5.00											
18.5	20.7	09646	2.2	2.2	4A13	.14	.23	.84	10.00											
20.7	22.9	09647	2.2	2.2	4A13	.20	.04	.33	6.00											
22.9	24.9	09648	2.0	2.0	4A13	.10	.04	.40	6.00											
24.9	26.9	09649	2.0	2.0	4A13	.07	.03	.26	3.00											
26.9	28.9	09650	2.0	2.0	4A13	.09	.03	.33	4.00											
28.9	30.9	09651	2.0	2.0	4A13	.09	.04	.39	6.00											
30.9	33.0	09652	2.1	2.1	4A13	.10	.08	.24	7.00											
33.0	35.1	09653	2.1	1.9	4A13	.09	.04	.28	6.00											
38.5	40.4	09654	1.9	1.8	4A13	.12	.05	.29	7.00											
40.4	42.3	09655	1.9	1.9	4A13	.13	.05	.33	6.00											
42.3	44.2	09656	1.9	1.9	4A13	.22	.04	.30	8.00											
44.2	46.1	09657	1.9	1.4	4A13	3.21	.28	.03	.75	10.00		.41	2	12	14					
46.1	48.1	09658	2.0	2.0	4A13	3.89	.19	1.21	3.30	28.00		.89	2	23	25					
48.1	49.9	09659	1.8	1.8	4EA	4.57	.27	1.65	3.70	35.00		1.10	2	32	34					
49.9	51.6	09660	1.7	1.7	4A13	3.66	.04	2.50	3.20	45.00		.82	1	16	18					
88.6	90.6	09661	2.0	2.0	5A16	2.98	.02	.32	.60	8.00		.27	1	3	5					
90.6	92.8	09662	2.2	2.2	4A13	3.08	.03	2.60	4.60	43.00	46.00	.55	1	7	8					
92.8	93.2	09663	.4	.3	4G4	4.07	.03	4.30	7.30	69.00		.48		9	10					
93.2	94.5	09664	1.3	1.3	4A1	3.12	.03	2.60	4.00	51.00		.55	1	7	8					
97.7	98.7	09665	1.0	.9	4L0	3.20	.06	1.47	2.50	28.00		.41	2	6	9					
98.7	99.3	09666	.6	.6	4A1	3.33	.03	.71	1.32	19.00		.34	2	14	17					
99.3	100.7	09667	1.4	1.4	4E8	4.26	.23	1.87	1.95	32.00		.75	5	30	35					
100.7	102.0	09668	1.3	1.2	4E8	4.10	.20	2.04	1.00	31.00		1.23	7	27	34					
102.0	104.1	09669	2.1	2.1	4C8	3.82	.27	1.40	2.80	32.00		.62	4	20	25					
104.1	105.4	09670	1.3	1.3	4L3	3.11	.09	.40	.26	14.00		.34	2	5	8					
105.4	106.0	09671	.6	.6	4E0	3.17	.31	1.97	3.60	44.00		1.37	4	24	28					
106.0	106.7	09672	.7	.6	4G4	3.89	.11	3.90	8.40	70.00	70.00	.89	2	10	12					

DDH: FAGU146

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														S.G. W.R.
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAC %	HG %	MN %	AS %	BA %	
15.2	17.2	08501	2.0	1.9	4A0	3.18	.05	1.36	2.64	29.99		.75	11	12							
17.2	19.2	08502	2.0	2.0	4A0	3.18	.08	.92	1.51	26.00		.89	11	12							
19.2	21.2	08503	2.0	2.0	4A0	3.22	.05	.97	1.42	26.00		.81	13	14							
21.2	23.2	08504	2.0	2.0	4A0	3.08	.05	1.12	1.86	27.99		.75	7	8							
23.2	25.2	08505	2.0	2.0	4A4	3.14	.05	2.89	4.50	43.00		1.03	1	6	8						
25.2	27.9	08506	2.7	2.7	4A4	3.06	.04	2.70	4.50	39.00		.68	1	4	5						
27.9	29.5	08507	1.6	1.6	4DL4	3.33	.07	4.40	5.90	69.00		1.10	4	8	13						
29.5	31.2	08508	1.7	1.6	4A14	3.35	.05	8.10	13.09	143.00	149.00	1.10	2	5	7						
31.2	32.4	08509	1.2	.9	4L4	3.37	.13	3.39	3.49	54.00		.95	3	13	16						
39.1	41.6	08510	2.5	2.5	4ADL	3.29	.16	1.71	3.49	37.00		.68	1	12	14						
44.1	46.9	08511	2.8	2.8	4A0	3.45	.14	1.25	2.29	28.99		1.43	1	17	18						
46.9	47.9	08512	1.0	1.0	4A0	3.74	.24	1.05	.55	31.99		1.30	1	25	27						
47.9	49.1	08513	1.2	1.1	4D4	4.25	.20	6.50	9.50	110.99		1.70	1	24	26						



DDH: FAGU148

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														S.G. W.R.
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAC %	HG %	MN %	AS %	BA %	
3.6	5.6	11781	2.0	2.0	4L41	2.89	.02	1.74	1.45	33.00		.89	3	1	5						
5.6	7.6	11782	2.0	2.0	4L41	2.85	.02	1.71	2.39	27.00		.55	2	1	3						
7.6	9.8	11783	2.2	2.2	4L41	2.85	.02	2.29	4.09	35.00		1.23	1		2						
10.5	12.8	11784	2.3	2.2	4CA		.07	.47	.77	10.00											
27.3	29.3	11785	2.0	1.8	4A41	2.81	.11	3.20	4.79	61.99		1.23	1	3	5						
29.3	31.3	11786	2.0	2.0	4A41	2.91	.05	2.10	3.10	38.00		1.16	1	4	5						
31.3	33.4	11787	2.1	2.1	4A41	2.99	.11	1.81	4.09	29.99		1.37	1	5	6						
38.1	40.1	11788	2.0	2.0	4A14	3.47	.07	3.00	4.29	49.00		1.85	3	15	18						
40.1	42.7	11789	2.6	2.6	4A14	3.72	.11	3.20	4.20	47.00		1.85	1	20	21						
42.7	43.8	11790	1.1	1.1	4A14	3.31	.05	5.20	6.70	74.00		1.85	1	7	9						
43.8	45.3	11791	1.5	1.5	4A14	3.43	.08	5.50	7.59	84.00		1.37	1	10	12						
45.3	46.8	11792	1.5	1.2	4A14	3.31	.05	3.29	3.79	55.00		1.78	1	11	12						
46.8	48.8	11793	2.0	2.0	4A10	2.89	.02	1.46	3.20	26.00	27.99	.47		2	3						
50.4	51.3	11794	.9	.8	4A10	2.89	.02	1.43	3.39	25.00		.47	1		1						
51.3	53.3	11795	2.0	1.6	4A30	3.04	.02	1.83	2.89	30.99		.89		6	7						
53.3	55.3	11796	2.0	1.6	4A43	3.27	.04	2.60	3.60	55.00		1.10	1	11	12						
55.3	57.3	11797	2.0	2.0	4A43	3.14	.02	3.10	5.59	58.99		2.39		8	9						
57.3	59.3	11798	2.0	1.6	4A43	3.24	.05	3.29	6.99	62.99		1.16	1	8	10						
59.3	61.3	11799	2.0	.8	4A43	3.18	.02	2.79	5.29	56.99		1.10	1	9	10						
61.3	62.9	11800	1.6	1.6	4A43	3.35	.05	3.20	5.20	55.99		1.58	1	11	12						
62.9	64.2	11801	1.3	1.3	4A4	3.04	.02	1.94	3.29	33.00		.68		6	7						
64.2	65.2	11802	1.0	1.0	4A14	2.87	.04	1.87	3.39	30.99	28.99	.47		1	2						





DDH: FAGU151

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----															
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAC %	HG %	MN %	AS %	BA %	S.G. W.R.	
.0	2.2	06862	2.2	1.6	4E4	4.06	.14	6.29	10.80	102.00		2.60	1	18	20							
2.2	2.8	06863	.6	.6	4E*4	4.29	.34	6.09	8.50	89.00	85.00	2.19	2	27	30							
2.8	4.1	06864	1.3	1.2	4E4	4.96	.29	10.50	15.99	137.00		4.11	1	25	26							
4.1	4.6	06865	.5	.4	4G0	5.00	.08	7.20	.80	112.99		1.10		17	18							
4.6	6.1	06866	1.5	1.3	4E4	4.80	.04	4.70	5.79	61.99		1.16	2	19	21							
6.1	7.4	06867	1.3	1.3	4B5	3.41	.07	.11	.14	6.00		.68	2	14	16							
7.4	9.1	06868	1.7	1.7	4A1	3.18	.01	.08	.08	6.99		.55	1	8	9							
9.1	11.1	06869	2.0	2.0	4A41	3.18	.02	2.10	3.60	34.00		.55	1	10	11							
11.1	13.1	06870	2.0	2.0	4A41	3.24	.02	2.50	4.40	44.00		.75		10	10							
13.1	14.3	06871	1.2	1.2	4A41	3.41	.13	2.89	6.50	55.99		1.64	1	13	14							
14.3	15.4	06872	1.1	1.1	4A41	3.39	.14	4.20	8.30	75.00		1.37	1	11	12							
15.4	16.7	06873	1.3	1.0	4D4	3.89	.22	9.69	10.90	151.00	145.00	1.51	1	15	17							
16.7	18.3	06874	1.6	1.6	4E4	4.13	.20	5.50	6.00	92.00		2.06	1	23	24							
18.3	20.7	06875	2.4	1.9	4E4	4.25	.33	3.49	3.60	56.99		1.85	2	30	32							
54.6	55.4	06876	.8	.8	4G41	4.79	.13	9.00	8.40	134.00		2.47	3	15	18							
55.4	57.8	06877	2.4	2.1	4E0	4.69	.22	2.20	1.27	39.00		2.47	2	35	37							
57.8	58.3	06878	.5	.4	4G41	4.86	.05	10.69	11.09	182.00		2.74	1	13	14							
58.3	60.1	06879	1.8	1.7	4E4	4.80	.17	3.89	3.39	56.99		.81	1	30	32							
60.1	62.4	06880	2.3	2.1	4E48	4.73	.14	13.40	12.30	177.00		2.39	8	15	23							
62.4	65.1	06881	2.7	1.9	4E4	4.58	.65	7.59	6.20	137.00		2.25	3	24	27							

DDH: FAGU152

-----DEPTHS-----				-----ASSAYS-----																	
FROM	TO	SAMPLE NO.	INT. REC.	ROCK UNIT	S.G. PULP	CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PC %	PY %	TOT FE	BAG %	HG %	MN %	AS %	BA %	S.G. W.R.	
14.1	14.5	08550	.4	.3	4D7		.02	1.88	4.50	31.99											
18.6	19.4	08551	.8	.5	4A4	3.33	.08	2.04	3.99	31.99			1.03	1	14	15					
19.4	20.9	08552	1.5	1.2	4C0	3.20	.16	.95	2.39	13.00	15.99		.47	1	12	14					
21.3	22.9	08553	1.6	1.2	4D0	3.04	.05	2.70	2.79	29.99			1.03		6	6					
22.9	24.4	08554	1.5	1.2	4D0	3.00	.07	3.20	3.79	39.00			1.10		3	4					
24.4	26.4	08555	2.0	1.9	4A0	2.93	.05	.91	1.13	14.99			.47		3	4					
26.4	28.4	08556	2.0	2.0	4A0	2.91	.04	.23	.57	3.99			.40		4	5					
28.4	30.3	08557	1.9	1.9	4A0	2.91	.04	.38	.55	6.99			.40	1	3	5					
33.5	34.5	08558	1.0	.8	4D4	2.91	.02	3.49	6.79	52.00			.47	3	3	6					
35.0	37.0	08559	2.0	2.0	4A0	3.16	.02	1.50	2.89	24.00			.75		11	11					
37.0	39.3	08560	2.3	2.3	4A4	3.37	.08	2.08	4.70	34.00			.95		15	16					
39.3	40.9	08561	1.6	1.6	4AE4	3.85	.22	3.49	7.70	65.00			1.16	2	18	21					
40.9	42.9	08562	2.0	2.0	4AE4	3.49	.17	1.87	4.29	38.00	41.00		1.23	1	14	16					
42.9	45.0	08563	2.1	2.1	4DE	4.13	.20	3.60	4.50	65.00			1.78	2	24	27					
45.0	46.7	08564	1.7	1.7	4CA	3.54	.28	.39	.91	20.00			1.10	1	20	21					

DDH: FAGU153

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													S.G. W.R.	
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAD %	HG %	MN %	AS %		BA %
.0	3.0	06836	3.0	1.5	4A4	3.49	.04	5.09	10.09	82.00		1.10	1	11	12						
3.0	5.3	06837	2.3	2.1	4A4	3.37	.11	3.20	6.09	69.00		1.16	1	14	15						
5.3	7.3	06838	2.0	2.0	4A4	3.35	.07	4.40	7.99	71.00		1.10	1	11	12						
7.3	9.1	06839	1.8	1.8	4A4	3.35	.05	4.79	12.69	82.00		1.23	1	7	8						
9.1	11.3	06840	2.2	2.1	4A4	3.35	.02	5.00	11.50	84.00		1.16	1	10	11						
11.3	13.1	06841	1.8	1.8	4A4	3.62	.07	4.70	8.80	79.00		1.43	1	15	16						
13.1	15.2	06842	2.1	2.1	4A4	3.37	.05	3.20	8.10	59.99		1.10	1	13	14						
15.2	16.8	06843	1.6	1.6	4A4	3.25	.05	1.68	4.20	35.00	31.99	.75	1	13	14						
16.8	18.3	06844	1.5	1.5	4A31	3.66	.05	1.62	3.79	38.00		.89	1	21	23						
18.3	19.8	06845	1.5	1.5	4A41	3.47	.02	1.62	4.29	35.00		1.58	1	16	17						
19.8	21.7	06846	1.9	1.5	4A41	3.24	.11	1.89	4.09	36.00		1.91	1	12	13						
21.7	23.2	06847	1.5	1.5	4A41	3.33	.08	2.89	6.90	55.99		1.91	1	13	14						
23.2	25.2	06848	2.0	1.6	4E0	4.53	.31	.66	1.07	25.00		2.39	1	40	42						
25.2	26.9	06849	1.7	1.6	4E0	4.66	.27	.82	1.56	25.00		1.91	1	40	42						
26.9	29.6	06850	2.7	2.7	4A41	3.45	.13	3.79	7.59	69.00		2.06	1	14	15						
29.6	30.5	06851	.9	.7	4E0	4.70	.24	1.82	1.78	36.00		1.03	1	40	42						
30.5	32.0	06852	1.5	1.4	4E4	4.42	.28	6.00	9.30	103.00		1.16	2	35	37						
32.0	33.5	06853	1.5	1.4	4AE4	3.66	.20	5.70	7.40	121.99	98.00	1.03	1	16	18						
33.5	35.1	06854	1.6	1.0	4E41	4.45	.07	11.50	19.60	185.00		2.87	2	16	18						
35.1	35.6	06855	.5	.4	4G4	4.78	.24	7.99	15.30	162.00		4.05	2	20	22						
35.6	36.6	06856	1.0	.8	4E4	4.37	.13	6.29	13.00	112.99		1.10	3	14	18						
36.6	37.0	06857	.4	.4	4A1	3.52	.08	2.29	2.60	52.00		1.98	1	15	17						
37.0	38.1	06858	1.1	1.0	4G4	4.75	.24	6.09	7.70	114.99		2.12		30	30						
38.1	40.0	06859	1.9	1.4	5C4	3.37	.05	.69	.61	15.99		4.66	4	11	16						
40.0	41.6	06860	1.6	1.2	4G4	4.94	.28	6.99	9.40	136.00		2.47		22	23						
41.9	42.7	06861	.8	.8	4A1	3.45	.05	.89	1.58	19.00		1.10	1	15	16						

DDH: FAGU154

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAO %	HG %	MN %	AS %	BA %	S.G. W.R.
1.2	2.9	08415	1.7	1.7	4A4	3.06	.05	2.70	6.00	41.00		.62	1	6	7						
2.9	4.6	08416	1.7	1.7	4A4	3.16	.07	3.10	5.09	50.00	52.00	1.58	1	9	10						
4.6	6.4	08417	1.8	1.8	4A4	3.68	.17	5.29	10.90	96.00		1.51	1	16	17						
6.4	7.1	08418	.7	.6	4E4	4.46	.01	9.59	15.30	161.00		1.10	1	24	25						
7.1	8.8	08419	1.7	1.7	4A4	3.27	.05	3.00	6.59	51.00		1.03	1	11	12						
8.8	10.6	08420	1.8	1.8	4A4	3.02	.02	1.58	3.79	30.99		.40		6	7						
10.6	12.4	08421	1.8	1.8	4A4	3.22	.02	2.39	5.59	41.00		.47	2	9	11						
12.4	14.2	08422	1.8	1.8	4A4	3.29	.07	3.29	6.79	57.99		.68	1	12	13						
14.2	15.3	08423	1.1	1.1	4A4	3.39	.10	4.40	11.09	74.00		.75	2	9	12						
15.3	16.5	08424	1.2	1.1	4A0	3.41	.10	.81	2.70	25.00		1.16	1	17	18						
16.5	17.8	08425	1.3	1.3	4A4	3.35	.08	4.09	8.69	75.00		.81	2	11	13						
17.8	18.8	08426	1.0	1.0	5D6	2.93	.01	.26	.16	6.00	7.99	.20	5	3	8						
18.8	20.8	08427	2.0	2.0	4A4	3.06	.02	2.50	5.40	47.00		.68	2	5	7						
20.8	22.8	08428	2.0	2.0	4A4	3.33	.14	5.09	8.40	94.00		1.03	1	7	9						
22.8	24.8	08429	2.0	2.0	4A0	3.49	.20	1.58	1.90	38.00		1.78	1	18	19						
24.8	26.8	08430	2.0	2.0	4A4	3.52	.20	3.20	5.29	69.00		1.63	1	16	17						









DDH: FAGU159

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----												
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAO %	HG %	MN %	AS %
19.7	21.7	09524	2.0	2.0	4A0	.09	.24	.52	15.00										
21.7	23.7	09525	2.0	.9	4A0	.17	.08	1.05	20.00										
23.7	25.7	09526	2.0	1.7	4A0	.12	1.00	.22	41.00										
25.7	27.7	09527	2.0	1.6	4A0	3.10	.34	.59	16.00			.69	14	14					
27.7	29.0	09528	1.3	.5	4A4	3.59	.09	4.30	7.80	73.00	72.00	1.85	14	14					
29.0	30.5	09529	1.5	1.1	4D4	3.53	.20	7.10	11.60	127.00		2.06	15	15					
30.5	30.9	09530	.4	.4	4E4	4.43	.19	8.00	16.10	139.00		1.85	3	24	28				
30.9	32.0	09531	1.1	.7	4A4	3.14	.12	1.39	2.90	31.00		.89	2	12	15				
52.3	54.3	09532	2.0	2.0	4EA	3.65	.09	5.10	7.30	77.00		1.71	5	17	22				
54.3	56.3	09533	2.0	1.9	4EA	3.68	.20	.92	3.20	26.00		1.58	2	26	28				
56.3	57.9	09534	1.6	1.5	4EA	3.69	.19	2.80	2.80	59.00		1.78	1	26	27				
57.9	60.0	09535	2.1	2.1	4A13	3.36	.08	1.27	3.20	23.00		1.10	2	18	20				
60.0	61.5	09536	1.5	1.5	4E4	3.85	.13	4.00	6.50	69.00		1.71	1	16	17				
61.5	63.0	09537	1.5	1.5	4A14	3.59	.08	1.35	3.50	23.00		1.51	1	24	26				
63.0	64.0	09538	1.0	.5	4D0	3.58	.16	2.00	5.50	29.00	33.00	2.33	2	15	17				
64.0	65.3	09539	1.3	1.3	4A13	3.30	.11	.40	.79	10.00		1.37	21	21					
65.3	67.3	09540	2.0	1.3	4E0	3.81	.18	.58	1.09	15.00		1.65	1	30	31				
67.3	69.3	09541	2.0	2.0	4E0	3.51	.15	2.05	3.20	43.00		1.92	23	24					
69.3	71.1	09542	1.8	1.5	4E0	3.62	.09	.70	2.90	18.00		1.37	1	28	30				
71.1	73.2	09543	2.1	2.1	4A14	2.87	.02	1.91	5.20	24.00		.62	1	3	5				
73.2	74.7	09544	1.5	.8	4L14	2.84	.04	2.60	5.70	35.00		.75	1	2					
74.7	76.2	09545	1.5	1.3	4L14	2.96	.06	3.30	8.30	52.00		.75	1	3	4				



DDH: FAGU151

---DEPTHS---			SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													S.G. W.R.
FROM	TO	CU %						PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAG %	HG %	MN %	AS %	BA %	
2.7	4.7	09546	2.0	1.3	4A13		.07	.54	1.05	12.00											
4.7	6.6	09547	1.9	1.0	4A13		.15	.19	.83	10.00											
6.6	8.5	09548	1.9	1.9	4A13		.16	.12	.59	8.00											
8.5	10.4	09549	1.9	1.9	4A13	3.05	.10	.35	.85	10.00		.55	2	15	17						
10.4	12.3	09550	1.9	1.9	4A13	3.31	.14	1.05	2.50	16.00		.96	1	18	20						
12.3	13.7	09551	1.4	1.4	4A34	3.37	.13	2.08	2.60	41.00		1.10	1	18	20						
13.7	14.7	09552	1.0	1.0	4E1	3.87	.26	1.53	1.86	30.00		2.19	1	28	30						
14.7	15.7	09553	1.0	1.0	4D4	3.47	.06	5.00	4.10	76.00		1.44	1	15	17						
15.7	17.2	09554	1.5	1.5	4D4	3.70	.08	5.70	8.30	80.00		1.37	2	15	17						
17.2	19.0	09555	1.8	1.8	4A34	3.60	.11	3.10	3.50	47.00		1.17	1	19	20						
19.0	20.1	09556	1.1	1.1	4A13	3.62	.23	2.70	1.11	47.00		1.37	1	21	23						
20.1	21.8	09557	1.7	1.7	4A4	3.39	.16	3.90	3.70	63.00		1.44	1	13	15						
21.8	23.5	09558	1.7	1.6	4A4	3.34	.10	6.40	11.60	106.00	109.00	1.71	2	9	11						
23.5	23.9	09559	.4	.4	4D4	3.92	.14	7.30	16.20	113.00		2.81	1	14	16						
23.9	25.2	09560	1.3	1.3	4E*4	4.81	.19	6.40	11.60	114.00		1.85	1	29	30						
25.2	26.6	09561	1.4	1.4	4E*4	4.80	.06	6.20	10.40	124.00		1.17		29	30						
26.6	28.8	09562	2.2	2.2	4A4	3.69	.10	7.20	9.70	123.00		1.37	1	10	12						
28.8	31.0	09563	2.2	2.2	4A4	3.68	.07	5.40	8.10	87.00		1.58	1	13	15						
31.0	33.2	09564	2.2	2.2	4D4	3.72	.06	6.50	9.80	104.00		1.58	2	10	13						
33.2	33.6	09565	.4	.4	4E18	4.47	.06	2.90	2.40	44.00		1.51	3	29	33						
33.6	35.2	09566	1.6	1.5	4D0	4.06	.08	2.40	3.60	37.00		1.10	2	19	21						
35.2	37.2	09567	2.0	2.0	4A314	3.52	.09	2.80	3.40	43.00		1.23	1	13	14						
37.2	39.2	09568	2.0	2.0	4A314	3.41	.09	3.50	5.80	49.00	46.00	1.44	1	16	17						
39.2	41.2	09569	2.0	2.0	4A314	3.56	.10	2.60	3.70	29.00		1.10	1	13	14						
41.2	43.0	09570	1.8	1.8	4E14	4.01	.19	2.05	3.40	30.00		1.03	1	25	27						
43.0	45.2	09571	2.2	2.1	4C0	3.94	.33	.10	.87	10.00		.75	2	26	28						
45.2	47.1	09572	1.9	1.9	4A13	3.36	.25	.14	.36	15.00		.96	1	20	22						
47.1	48.5	09573	1.4	1.4	4C0	3.90	.32	.26	.96	16.00		1.03	1	23	25						
48.5	49.9	09574	1.4	1.4	4C0	3.94	.28	.50	1.08	17.00		1.23	2	23	26						
49.9	51.6	09575	1.7	1.6	4D4	3.85	.15	5.20	3.90	86.00		2.40	1	18	20						
51.6	53.3	09576	1.7	1.4	4D4	3.75	.15	4.20	4.50	64.00		1.71	2	17	19						
54.3	55.1	09577	.8	.8	4L4	3.21	.05	1.71	3.60	24.00		.34	2	3	6						
55.1	56.1	09578	1.0	.7	4E14	3.68	.07	6.70	8.00	93.00		1.23	5	8	13						

DDH: FAGU162

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAC %	HG %	MN %	AS %	BA %
10.0	12.0	14031	2.0	1.8	4A0	3.04	.05	1.96	.68	29.99		.75	1	6	8					
12.0	14.0	14032	2.0	2.0	4A0	3.00	.05	.66	.31	13.99		.62		7	8					
14.0	16.0	14033	2.0	1.9	4A0	3.14	.07	1.40	1.14	24.00		.68		11	12					
16.0	18.0	14034	2.0	1.7	4A0	3.10	.07	1.30	1.22	24.00		.75	1	8	10					
18.0	19.6	14035	1.6	1.5	4A0	3.02	.05	.86	.78	17.00		.55		9	10					
19.6	21.6	14036	2.0	2.0	4C5	2.95	.05	.85	1.38	15.99		.40		4	4					
21.6	23.4	14037	1.8	1.5	4C5	2.87	.05	1.15	2.41	20.00		.55		3	3					
23.4	25.0	14038	1.6	1.0	4A0	3.27	.13	.93	2.27	19.00		1.70		15	16					
25.0	26.6	14039	1.6	1.5	4A4	3.16	.07	2.19	3.68	40.00		1.10		11	11					
26.6	27.7	14040	1.1	1.1	4E4	4.37	.20	3.93	5.90	86.00		1.37	1	29	31					
34.5	35.7	14041	1.2	1.1	4GL		.02	3.79	7.90	84.00										
49.2	50.7	14042	1.5	1.4	4G4	4.00	.02	6.09	11.80	127.99		.81	1	7	9					
50.7	52.3	14043	1.6	1.5	4G4	3.99	.16	7.40	15.09	131.00		1.85	1	9	11					
52.3	54.0	14044	1.7	1.7	4G4	4.34	.07	6.79	13.09	143.00		1.03	1	11	12					
100.1	102.0	14045	1.9	1.8	4AED	3.43	.17	2.00	2.85	29.99		1.98	3	17	20					
102.0	104.0	14046	2.0	2.0	4D0	3.50	.32	1.85	3.18	33.00		.95	4	17	21					
104.0	105.7	14047	1.7	1.5	4C0	3.52	.29	1.34	2.02	26.00		.89	4	17	22					
105.7	107.6	14048	1.9	1.7	4ALD	3.20	.11	1.76	2.50	31.99		.40	3	10	14					
107.6	110.5	14049	2.9	2.9	4C5		.23	.58	.68	13.99										
110.5	112.8	14050	2.3	1.9	4A0		.02	1.13	1.69	19.00										
132.4	133.1	14052	.7	.7	4E4		.04	3.83	6.59	80.00										
142.4	144.0	14053	1.6	1.6	4GA	3.52	.05	1.88	3.68	37.00		.47	2	10	13					
144.0	145.5	14054	1.5	1.2	5C*	3.18	.01	.80	2.24	17.00		.34	3	6	10					
145.5	147.2	14055	1.7	1.6	4GH	4.51	.14	4.36	7.20	77.00		1.58	6	18	24					

DDH: FAGU163

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														S.G. W.R.
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAC %	HG %	MN %	AS %	BA %	
.0	2.1	07646	2.1	.2	4C8	3.69	.20	.14	1.55	15.00		1.30	1	25	27						
2.1	4.1	07647	2.0	1.3	4C8	3.46	.23	.20	1.31	12.00		.55	3	20	23						
4.1	6.1	07648	2.0	2.0	4C8	3.39	.25	.33	.92	17.00		.75	2	19	21						
6.1	8.0	07649	1.9	1.9	4C8	3.48	.24	1.54	2.50	39.00		1.10	2	19	21						
19.4	21.0	07650	1.6	1.5	4H*	3.66	.09	3.50	2.80	53.00		.21	15	10	25						
60.4	61.8	07651	1.4	1.3	4E4	4.64	.17	5.40	9.10	102.00		1.71	1	15	16						
61.8	63.4	07652	1.6	1.6	4E4	4.40	.16	3.90	7.70	71.00		1.65	1	17	19						
89.6	91.0	07653	1.4	.6	4C0	3.53	.27	1.09	.60	27.00		.89	2	19	22						
91.0	93.3	07654	2.3	1.3	4D8	3.90	.13	3.20	2.50	46.00	43.00	.75	7	20	27						
93.3	95.0	07655	1.7	1.6	4L8	3.81	.29	1.60	1.56	28.00		.48	17	14	31						



DDH: FAGU165

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAO %	HG %	MN %	AS %	BA %
.0	2.3	07358	2.3	.9	4A34	3.46	.24	3.30	4.90	47.00		1.99	1	18	19					
2.3	4.4	07359	2.1	1.8	4A3	3.35	.21	1.48	2.05	24.00		.89	1	18	20					
4.4	6.1	07360	1.7	1.7	4C0	3.46	.25	.13	.75	10.00		.69	2	22	24					
6.1	7.6	07361	1.5	1.4	4C0	3.41	.26	.08	.53	11.00		.55	2	21	23					
7.6	9.5	07362	1.9	1.8	4C0	3.57	.27	.91	1.40	30.00		1.03	2	24	26					
18.3	20.7	07363	2.4	1.9	4E1		.27	.67	.82	27.00										
20.7	22.9	07364	2.2	2.1	4E1		.35	.14	.65	31.00										
22.9	25.3	07365	2.4	2.2	4C0	3.56	.34	.12	1.17	14.00		.62	3	20	23					
25.3	27.4	07366	2.1	2.0	4C5	3.62	.22	1.57	1.63	46.00		1.10	1	22	24					
27.4	30.1	07367	2.7	2.2	4C0		.51	.12	.72	20.00										
30.1	32.5	07368	2.4	2.2	4C0		.22	.07	.42	12.00										
32.5	33.1	07369	.6	.6	4C0	3.08	1.09	.03	.34	30.00		1.99	4	13	17					
33.1	35.0	07370	1.9	1.9	4C0	3.64	.51	.07	.53	17.00		.75	4	22	26					
35.0	36.9	07371	1.9	1.9	4E1	3.99	.43	1.25	2.02	37.00	33.00	1.30	4	30	35					
36.9	39.6	07372	2.7	2.3	4E1	4.49	.31	1.46	2.60	36.00		1.58	2	37	40					
39.6	41.7	07373	2.1	2.0	4E1	4.21	.32	1.00	1.09	31.00		1.78	2	36	38					

DDH: FAGU166

-----DEPTHS-----		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														S.G. W.R.
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAC %	HG %	MN %	AS %	BA %	
35.1	37.8	14056	2.7	2.4	4EAC	3.45	.05	3.62	6.20	69.00		.81	1	13	14						
37.8	40.2	14057	2.4	2.4	4AC	3.35	.04	2.25	2.22	36.00		.89		13	14						
47.1	49.1	14058	2.0	1.8	4C5	2.97	.05	.93	1.61	20.00		.75		4	5						
51.6	54.2	14059	2.6	2.6	4C0	2.93	.04	.92	1.85	19.00		.55	1	3	5						
113.5	115.3	14060	1.8	1.8	4AG	3.72	.08	2.71	4.75	55.00		.75	1	13	14						
115.3	117.3	14061	2.0	2.0	4E4	4.36	.17	2.98	4.13	59.99		.55	1	28	29						
117.3	119.3	14062	2.0	1.8	4E4	4.33	.20	2.56	3.45	55.99		.62	1	30	31						
119.3	120.2	14063	.9	.9	4E4	4.20	.16	2.95	4.75	71.00		1.03		25	25						
121.9	123.6	14064	1.7	1.5	4A0		.08	1.03	1.60	20.00											
130.3	132.3	14065	2.0	2.0	4C0		.05	.34	.59	9.00											
132.3	134.3	14066	2.0	2.0	4C0		.11	1.18	2.06	25.00											
134.3	136.1	14067	1.8	1.6	4C0		.05	.48	.83	12.00											
138.3	140.0	14068	1.7	1.7	4A30	3.29	.14	1.51	2.10	29.99		.95	1	15	16						
140.0	141.7	14069	1.7	1.7	4A34	3.52	.10	5.00	7.59	80.00		1.64	1	14	15						
141.7	143.5	14070	1.8	1.7	4A34	3.39	.23	3.43	4.32	55.00		1.03	1	13	15						
143.5	145.9	14071	2.4	2.4	4C3		.40	.56	.84	20.00											
145.9	148.3	14072	2.4	2.4	4C3		.41	.51	.58	22.00											
148.3	150.9	14073	2.6	1.4	4E0	4.67	.14	1.47	.88	34.00		.81	1	37	38						
150.9	151.5	14074	.6	.6	4A4	3.56	.11	3.89	5.20	60.99		1.51	2	15	18						

DDH: FAGU167

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													S.G. W.R.
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAC %	HG %	MN %	AS %	
.9	1.8	07343	.9	.9	4C0		.25	.21	.75	9.00										
1.8	4.0	07344	2.2	1.9	4C0	3.54	.28	.28	1.03	19.00		.96	2	19	22					
4.0	6.1	07345	2.1	2.1	4C0	3.61	.28	1.37	2.30	33.00		1.99	2	19	22					
11.6	12.8	07346	1.2	1.2	4H14	3.50	.26	5.10	6.00	84.00		1.51	9	9	18					
32.2	34.4	07347	2.2	1.3	4G4	4.26	.15	5.00	8.60	76.00		.75		21	22					
34.4	36.6	07348	2.2	2.1	4G4	4.83	.12	4.40	6.60	68.00		1.03		27	27					
36.6	38.3	07349	1.7	1.7	4E4	4.71	.14	3.90	4.60	60.00		1.92		37	38					
38.3	40.0	07350	1.7	1.5	4E4	4.57	.20	4.40	6.60	87.00		1.44		28	29					
40.0	42.1	07351	2.1	2.1	4G4	4.54	.11	4.20	7.10	77.00		.96		18	18					
42.1	42.6	07352	.5	.5	5A16	3.33	.10	2.80	3.80	60.00		.96		10	11					
42.6	44.3	07353	1.7	1.7	4G4	4.51	.13	5.70	10.70	102.00		1.44	1	16	17					
44.3	45.7	07354	1.4	1.4	4E4	4.46	.24	5.10	7.20	79.00		1.65	1	33	34					
45.7	46.2	07355	.5	.5	4G4	4.53	.11	8.10	12.70	139.00		1.10	1	19	20					
46.2	48.1	07356	1.9	1.5	4E4	4.29	.11	9.00	14.10	149.00	133.00	1.58	2	23	26					
48.1	49.2	07357	1.1	.9	4G4	4.26	.24	6.10	12.60	101.00		1.85	1	20	21					

DDH: FAGU168

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														S.G. W.R.
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAC %	HG %	MN %	AS %	BA %	
.0	1.9	14001	1.9	.0	4A4	3.99	.13	5.79	16.09	138.00		1.64	1	17	18						
1.9	3.8	14002	1.9	.0	4A4	3.08	.10	2.83	8.80	53.00		.47		5	5						
3.8	5.7	14003	1.9	.0	4A4	3.20	.02	4.02	9.40	74.00		.47		7	8						
5.7	7.6	14004	1.9	.0	4A4	3.10	.02	2.99	8.30	54.00		.20		5	5						
30.9	32.0	14005	1.1	.0	4E4S	4.01	.01	5.20	13.40	98.00		.47	1	18	20						
33.5	34.0	14006	.5	.0	4K4	3.93	.01	4.41	9.40	84.00		.47	1	19	21						
34.0	36.7	14007	2.7	.0	4A4	3.33	.02	3.74	6.79	71.00		.62		11	11						
36.7	38.1	14008	1.4	.0	4D3	3.62	.08	2.58	4.24	58.99		.75	5	16	21						
109.5	110.0	14009	.5	.0	4L14		.02	.34	.16	6.99											
110.0	110.8	14010	.8	.0	4A0		.08	.23	.17	6.99											
110.8	113.9	14011	3.1	.0	4A1		.07	.53	.34	13.99											
113.9	114.6	14012	.7	.0	5D4*		.02	.16	.27	6.00											
114.6	116.6	14013	2.0	.0	4A1		.11	.83	.97	20.00											
116.6	118.9	14014	2.3	.0	4E4	4.62	.17	4.42	7.99	90.00		1.23		24	24						
118.9	121.2	14015	2.3	.0	4G4	4.67	.05	5.20	9.59	92.00		.95		16	16						
121.2	123.4	14016	2.2	.0	4G4	4.65	.17	5.29	9.00	103.00		.95		18	19						
123.4	124.5	14017	1.1	.0	4E4	4.78	.26	4.02	6.50	103.00		1.30		30	31						
133.9	136.0	14018	2.1	.0	4EG	4.61	.32	2.47	2.45	46.00		1.51		36	37						
136.0	138.1	14019	2.1	.0	4EG	4.78	.26	2.39	3.56	61.99		1.85		35	36						
138.1	140.3	14020	2.2	.0	4G4	4.67	.14	4.02	8.33	85.00		1.58		24	24						
140.3	142.4	14021	2.1	.0	4G4	4.73	.14	4.67	9.00	84.00		2.33		17	17						
142.4	144.5	14022	2.1	.0	4G4	4.59	.14	5.70	9.00	94.00		1.85		23	23						
144.5	145.3	14023	.8	.0	4A34	3.35	.05	2.48	4.32	45.00		.81	1	13	14						
145.9	147.8	14024	1.9	.0	4A1		.05	.24	.67	11.00											
150.0	150.4	14025	.4	.0	4C0		.05	.11	.17	9.00											
150.4	152.5	14026	2.1	.0	4A0		.10	.83	1.40	22.00											
152.5	154.1	14027	1.6	.0	4E46	4.48	.28	3.25	5.70	56.99		1.03	1	28	30						
154.1	155.4	14028	1.3	.0	4D45	3.72	.20	3.93	8.59	81.00		2.06	2	18	21						
155.4	156.5	14029	1.1	.0	4D4	3.74	.17	4.79	6.59	81.00		2.12	2	18	20						



DDH: FAGU170

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														S.G. W.R.
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAG %	HG %	MN %	AS %	BA %	
1.0	2.9	14214	1.9	1.6	4A34	3.29	.04	2.14	3.72	46.00		.75	1	10	11						
2.9	4.8	14215	1.9	1.8	4A34	3.56	.02	3.91	7.29	70.00		.75	1	14	15						
4.8	6.7	14216	1.9	1.9	4A34	3.43	.05	2.10	3.39	50.00		.68	1	14	15						
6.7	8.7	14217	2.0	1.9	4A34	3.52	.05	2.79	5.59	58.99		.95	1	13	15						
8.7	10.7	14218	2.0	1.9	4C5	2.98	.02	.88	1.30	14.99		.75	1	2	3						
10.7	12.7	14219	2.0	2.0	4C5	3.02	.02	1.76	2.44	28.99		.55		1	2						
12.7	14.7	14220	2.0	1.7	4D5	3.06	.02	3.39	3.27	80.00		.68		2	3						
14.7	16.7	14221	2.0	1.5	4D5	3.10	.02	1.83	4.11	36.00		.34	1	2	3						
16.7	18.7	14222	2.0	1.8	4D5	3.08	.02	3.52	3.66	94.00		.34	1	1	2						
18.7	20.7	14223	2.0	1.5	4C5	3.06	.02	.91	3.06	19.00		.20	1		2						
20.7	23.0	14224	2.3	2.0	4C5		.01	.46	1.31	9.00											
23.0	25.1	14225	2.1	1.9	4C5		.02	.29	.82	6.99											
25.1	27.5	14226	2.4	2.0	4C5	3.00	.02	1.43	2.31	24.00		.27		2	3						
27.5	29.2	14227	1.7	1.4	4C5	3.02	.02	.79	1.27	15.99		.14	2	1	3						
30.4	32.8	14228	2.4	.4	4A0	3.52	.04	1.40	3.56	28.99		.47	2	12	14						
32.8	34.0	14229	1.2	.6	4KEA	3.35	.05	4.00	8.80	83.00		.40	1	8	9						
34.0	35.9	14230	1.9	1.0	4KE	3.87	.05	6.79	12.40	119.99		.34	1	15	17						
37.0	37.9	14231	.9	.9	4D\$4	3.97	.05	3.95	9.09	75.00		.40	2	18	20						
37.9	40.7	14232	2.8	2.5	4A34	3.31	.04	4.98	5.70	81.00		.68	1	9	10						
40.7	43.0	14233	2.3	1.6	4K4	3.52	.05	3.35	7.49	58.99		.55	2	3	5						
43.0	45.7	14234	2.7	2.3	4K4	3.72	.01	2.22	4.32	46.00		.40	1	19	21						
45.7	46.7	14235	1.0	.9	4E4	3.97	.14	6.29	9.59	134.00		1.43		20	20						
46.7	48.7	14236	2.0	1.7	4A4	3.35	.05	4.82	6.99	80.00		.95	1	10	11						
48.7	50.3	14237	1.6	1.0	4AE	3.39	.05	1.93	3.10	40.00		1.23	2	11	14						
50.3	52.5	14238	2.2	2.0	4A34	3.31	.05	4.79	6.50	73.00		.89		10	11						
52.5	54.8	14239	2.3	2.0	4A34	3.39	.05	3.31	3.91	52.00		1.16	4	12	16						

DDH: FAGU171

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														S.G. W.R.
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAO %	HG %	MN %	AS %	EA %	
.0	3.2	08139	3.2	2.4	4EC8	.48	.04	.33	11.00												
3.2	6.5	08140	3.3	2.2	4EC8	.47	.03	.40	8.00												
15.1	17.0	08141	1.9	1.8	5D4	3.14	.05	2.21	3.00	30.00			2.12	3	7	10					
17.0	17.7	08142	.7	.7	4G4	4.17	.28	6.80	9.20	133.00			1.78	2	22	24					

DDH: FAGU172

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														S.G. W.R.
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAO %	HG %	MN %	AS %	BA %	
.0	2.4	12949	2.4	1.0	4A4	3.16	.01	3.47	6.50	68.00		.34	2	4	6						
2.4	4.9	12950	2.5	1.6	4E4	4.00	.04	6.79	16.39	154.00		.81	1	13	15						
4.9	6.0	12951	1.1	1.1	4A4	3.06	.01	2.72	4.46	66.00		.40		3	4						
6.0	6.6	12952	.6	.6	4E154	3.37	.01	3.64	12.50	73.00		.40	1	9	10						
14.3	16.2	12953	1.9	1.9	4A4	3.60	.04	7.09	13.99	142.00		1.16	2	8	10						
16.2	18.1	12954	1.9	1.9	4A4	3.39	.01	6.40	6.79	120.99		.55	1	7	8						
18.1	20.0	12955	1.9	1.9	4A4	3.22	.02	3.87	6.00	67.00		.40	2	5	7						
20.0	21.9	12956	1.9	1.7	4A4	3.24	.01	3.12	7.09	58.99		.27		7	8						
21.9	23.8	12957	1.9	1.9	4A4		.02	3.68	4.09	70.00											
23.8	25.7	12958	1.9	1.9	4A4	3.10	.04	1.71	8.69	35.00		.27		6	7						
25.7	27.6	12959	1.9	1.9	4A4	3.22	.01	3.35	5.59	60.99		.20	1	5	6						
27.6	29.5	12960	1.9	1.5	4A4	3.24	.01	2.22	4.05	43.00		.20		8	9						
29.5	31.4	12961	1.9	1.9	4A4	3.14	.01	1.80	9.09	30.99		.20	1	5	6						
31.4	33.2	12962	1.8	1.8	4A4	3.45	.01	4.24	7.90	78.00		.47	1	10	11						
35.5	37.3	12963	1.8	1.8	4A4	3.35	.01	3.43	8.40	69.00		.14	1	9	10						
37.3	39.0	12964	1.7	1.7	4A4	3.22	.02	2.83	6.99	56.99		.40	1	8	9						
39.0	40.5	12965	1.5	1.5	4A4	3.66	.07	2.75	5.00	57.99		.89	1	16	18						
40.9	41.4	12966	.5	.4	4E*		.05	.93	1.37	22.00											
49.4	51.3	12967	1.9	1.9	4A4	3.49	.05	5.09	6.99	81.00		.89	1	11	13						
51.3	53.2	12968	1.9	1.9	4A4	3.41	.05	6.79	10.09	105.00		.95	1	7	9						
53.2	55.1	12969	1.9	1.9	4A4	3.27	.02	4.05	8.80	71.00		.47	1	7	8						
55.1	57.0	12970	1.9	1.9	4A4	3.33	.02	2.73	6.50	53.00		.40	1	10	11						
57.0	58.9	12971	1.9	1.9	4A4	3.47	.02	4.83	8.59	87.00		.62	1	10	11						
58.9	60.8	12972	1.9	1.9	4A4	3.33	.02	2.02	3.74	39.00		.89		12	13						
60.8	62.7	12973	1.9	1.9	4A0	3.39	.05	.47	1.27	12.00		.89	1	15	16						
62.7	64.6	12974	1.9	1.9	4A0		.05	.68	1.82	15.99											
90.0	92.2	12975	2.2	2.0	4L14		.02	.29	.63	6.00											
92.2	94.5	12976	2.3	2.3	4L14		.10	.31	.44	7.99											
94.5	96.5	12977	2.0	2.0	4A4	3.37	.11	3.02	3.95	51.00		1.03	1	12	14						
96.5	98.5	12978	2.0	2.0	4A4	3.41	.10	2.89	3.70	44.00		.81		14	15						
98.5	100.5	12979	2.0	2.0	4A3	3.83	.11	1.90	2.10	40.00		.95		16	17						
100.5	102.5	12980	2.0	2.0	4A3		.16	.47	.66	23.00											
102.5	104.5	12981	2.0	2.0	4A4	3.52	.07	3.58	3.77	43.00		.95		8	8						
104.5	106.5	12982	2.0	2.0	4A0	3.72	.13	1.61	2.77	28.99		1.16		13	14						
106.5	108.5	12983	2.0	2.0	4A34	3.83	.14	2.75	2.93	49.00		1.58	1	14	16						
108.5	110.5	12984	2.0	2.0	4A0	3.81	.14	1.11	2.19	25.00		1.37	1	16	18						
110.5	112.5	12985	2.0	2.0	4A0	3.52	.08	.82	1.15	19.00		1.03		11	12						
112.5	114.0	12986	1.5	1.5	4A0	3.79	.11	2.66	.83	41.00		1.10	1	15	16						
114.0	115.7	12987	1.7	1.7	4A3		.20	.34	.62	22.00											
115.7	116.6	12988	.9	.9	4E4	5.17	.14	9.69	15.49	172.00		1.58	1	21	23						
116.6	117.3	12989	.7	.7	4EG	5.36	.26	3.52	6.70	107.00		1.30		27	27						
117.3	118.7	12990	1.4	1.4	4E4	4.62	.14	2.60	2.68	49.00		1.37		36	36						
118.7	120.1	12991	1.4	1.4	4E0	4.78	.17	2.24	2.16	52.00		1.30		39	39						
120.1	121.9	12992	1.8	1.8	4GE4	4.59	.17	4.16	8.69	74.00		1.43	2	25	27						







DDH: FAGU176

-----DEPTHS-----		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														S.G. W.R.
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAG %	HG %	MN %	AS %	BA %	
27.9	29.5	14340	1.6	1.4	4A4	3.16	.01	3.89	8.30	74.00		.47	1	5	7						
29.5	30.9	14341	1.4	1.1	4A4	3.20	.05	3.20	7.40	78.00		.81	1	5	6						
58.6	61.1	14342	2.5	1.7	4A34	3.49	.05	4.76	8.40	77.00		.95	1	12	13						
61.1	62.8	14343	1.7	1.5	4E4	3.83	.08	1.73	3.41	39.00		1.37	1	21	23						
110.0	111.6	14344	1.6	1.5	4AL		.07	.58	.84	15.99											
111.6	113.2	14345	1.6	1.6	4A0		.08	.86	.98	20.00											
113.2	115.7	14346	2.5	2.5	4A31		.14	.69	.62	24.00											
115.7	117.3	14347	1.6	1.4	4E46		.17	5.00	7.99	77.00											
150.8	152.7	14348	1.9	1.8	4E46	4.54	.08	4.44	7.20	78.00		1.03	1	22	23						
152.7	154.6	14349	1.9	1.9	4E46	5.01	.35	6.40	9.50	118.99		.81		25	26						
154.6	157.0	14350	2.4	2.2	4E4	4.67	.28	3.10	3.85	50.00		.95		36	36						
157.0	159.5	14351	2.5	2.4	4E0	4.54	.29	1.82	3.08	38.00		.89		34	35						
159.5	162.0	14352	2.5	2.5	4A34	3.56	.08	4.28	8.30	75.00		1.43	1	14	15						



DDH: FAGU178

-----DEPTHS-----		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----													
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PC %	PY %	TOT FE	BAO %	HG %	MN %	AS %	BA %
.0	4.7	14297	4.7	1.9	4D5	3.33	.02	4.05	7.29	62.99		.81	1	8	10					
4.7	6.7	14298	2.0	2.0	4D5	3.24	.02	1.70	4.40	35.00		.40	1	10	11					
6.7	8.7	14299	2.0	1.8	4D5	3.16	.02	2.85	5.79	47.00		.47	1	6	7					
8.7	10.7	14300	2.0	2.0	4A4	3.18	.07	4.95	9.59	90.00		.68	3	2	5					
10.7	13.5	14301	2.8	2.5	4A4	3.08	.04	2.31	3.08	36.00		.81	1	6	8					
13.5	15.4	14302	1.9	1.9	4C0	3.08	.11	.41	.35	13.00		1.37	1	8	10					
15.4	17.4	14303	2.0	1.9	4A0	2.97	.04	3.29	1.07	39.00		.75		4	4					
17.4	19.2	14304	1.8	1.8	4C0	3.02	.07	3.08	1.22	36.00		.75	1	5	6					
20.1	22.3	14305	2.2	2.2	4D0	3.00	.04	2.64	2.37	35.00		.47	1	3	5					
22.3	24.5	14306	2.2	2.1	4C0	2.98	.04	1.15	1.55	19.00		.68	2	2	5					
24.5	26.0	14307	1.5	1.5	4C0	3.02	.02	1.49	2.41	24.00		.34	5		5					
26.0	27.5	14308	1.5	1.5	4D5	2.95	.01	2.50	3.83	43.00		.68	1		2					
27.5	29.0	14309	1.5	1.4	4C5	2.87	.01	1.33	2.56	26.00		.27	1		1					
32.8	34.8	14310	2.0	2.0	4A0		.05	.88	1.32	11.00										
34.8	37.4	14311	2.6	2.6	4A0	2.95	.02	1.98	2.02	27.00		.81		3	4					
37.4	39.7	14312	2.3	2.3	4ADE	3.27	.05	3.04	6.00	50.00		.68	1	9	11					
64.8	66.0	14313	1.2	1.2	4CA	3.12	.04	2.37	1.96	31.99		.40	2	6	9					
66.0	67.3	14314	1.3	1.3	5D4*	3.00	.01	.88	1.78	15.99		.20	6	1	7					
67.3	68.6	14315	1.3	.8	4DE	3.45	.08	2.17	4.79	47.00		.20	11	9	20					

DDH: FAGU179

					-----ASSAYS-----																
DEPTHS	SAMPLE	INT.	REC.	ROCK	S.G.	CU	PB	ZN	AG(AA)	AG(FA)	AU(FA)	PC	PY	TOT	BAO	HG	MN	AS	BA	S.G.	
FROM	TO	NO.		UNIT	PULP	%	%	%	G/MT	G/MT	G/MT	%	%	FE	%	%	%	%	%	W.R.	
.0	2.2	08536	2.2	1.7	4C0	3.65	.28	1.60	1.67	26.00		.75	3	20	23						
2.2	4.6	08537	2.4	2.3	4C0	3.74	.43	.28	1.03	16.00		.96	3	24	28						
4.6	5.3	08538	.7	.7	5B6	2.95	.03	.24	.51	5.00		.27	3	3	6						
5.3	6.3	08539	1.0	1.0	4C0	3.45	.24	2.00	3.20	39.00	41.00	1.44	3	17	21						
6.3	7.9	08540	1.6	1.4	4EA	3.65	.13	5.70	6.60	76.00		2.13	2	15	17						
7.9	9.9	08541	2.0	2.0	4D4	3.79	.19	7.50	11.10	115.00		2.26	2	14	17						
9.9	14.0	08542	4.1	2.3	4D4	3.71	.07	9.60	21.60	152.00		1.78	3	6	9						
14.0	16.1	08543	2.1	1.9	4D4	3.93	.06	9.60	22.40	165.00		2.06	2	8	10						
30.2	32.4	08544	2.2	2.2	4G4	4.33	.05	4.30	9.80	67.00		.89	1	15	16						
32.4	34.6	08545	2.2	2.2	4G4	4.60	.03	1.02	2.90	19.00		.34		22	23						
34.6	36.9	08546	2.3	2.3	4G4	4.69	.02	2.60	6.50	31.00		.55		21	22						
36.9	39.1	08547	2.2	1.9	4E4	4.61	.15	3.30	4.60	60.00		.96	1	31	33						
39.1	41.1	08548	2.0	2.0	4E4	4.67	.17	3.30	3.50	382.00		1.44	1	35	37						
41.1	45.7	08549	4.6	1.0	4E4	4.21	.20	3.80	3.90	52.00	51.00	1.17	1	31	32						

DDH: FAGU180

						-----ASSAYS-----															
---DEPTHS---	SAMPLE	INT.	REC.	ROCK	S.G.	CU	PB	ZN	AG(AA)	AG(FA)	AU(FA)	PO	PY	TOT	BAO	HG	MN	AS	BA	S.G.	
FROM	TO	NO.		UNIT	PULP	%	%	%	G/MT	G/MT	G/MT	%	%	FE	%	%	%	%	%	W.R.	
.0	2.1	14285	2.1	.4	4A41	3.64	.07	6.00	10.69	91.00		1.03	9	3	12						
2.1	3.8	14286	1.7	1.6	4C0		.11	.63	.66	10.00											
3.8	5.4	14287	1.6	1.4	4C0		.16	.47	.86	10.00											
5.4	7.0	14288	1.6	1.3	4A0		.08	.28	.72	6.00											
7.0	9.0	14289	2.0	1.5	4A0		.08	.28	.55	7.99											
9.0	11.0	14290	2.0	1.9	4A0		.04	.63	1.06	11.00											
11.0	13.1	14291	2.1	1.4	4A0		.05	.34	1.15	6.99											
13.1	15.2	14292	2.1	2.1	4A0		.08	.34	.64	13.00											
15.2	17.3	14293	2.1	2.0	4A0	3.02	.05	1.47	2.87	27.00		.34	1	6	7						
17.3	19.0	14294	1.7	1.6	4A0	3.14	.07	1.43	2.04	27.99		.81	1	10	11						
19.0	20.7	14295	1.7	1.6	4A4	3.35	.17	2.81	4.01	51.00		1.37	1	13	15						
20.7	22.2	14296	1.5	1.4	4A34	3.35	.13	4.25	5.40	63.99		.68	2	10	12						

DDH: FAGU181

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														
FROM	TO						CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAC %	HG %	MN %	AS %	BA %	S.G. W.R.
.0	1.5	05229	1.5	1.2	4E4	4.52	.16	6.37	13.55	134.00		.96	4	23	27						
1.5	3.0	05230	1.5	1.5	4E4	4.13	.15	9.20	15.21	149.00		.69	3	20	23						
3.0	4.5	05231	1.5	1.5	4E4	4.83	.25	7.33	12.03	91.00	90.00	1.03	2	26	28						
4.5	6.0	05232	1.5	1.5	4E4	4.84	.16	4.01	9.15	79.00		.89	3	33	36						
6.0	7.4	05233	1.4	1.4	4E4	4.38	.24	5.95	12.82	94.00		1.78	3	22	25						
7.4	8.0	05234	.6	.6	4G4	4.76	.20	4.86	10.01	113.00		1.65	1	15	17						
8.0	10.0	05235	2.0	2.0	4D4	3.99	.10	9.80	21.30	167.00		1.30	3	11	14						
10.0	11.8	05236	1.8	1.8	4D4	3.85	.06	12.60	23.70	199.00		1.51	3	7	10						
49.8	51.3	05237	1.5	1.5	4G4	4.42	.12	4.68	9.05	105.00		.89	1	20	22						
51.3	52.8	05238	1.5	1.4	4G4	4.62	.14	6.47	11.90	106.00		1.23	1	13	14						
52.8	54.3	05239	1.5	1.5	4G4	4.69	.12	5.19	9.73	94.00		1.10	1	15	16						
54.3	55.8	05240	1.5	1.5	4G4	4.32	.11	4.99	9.07	106.00		.55	1	13	14						
55.8	57.3	05241	1.5	1.5	4G4	3.44	.07	2.20	5.21	45.00	44.00	.41	2	8	10						
57.3	58.8	05242	1.5	1.5	4G4	4.67	.20	5.78	8.07	118.00		1.30	1	21	22						
58.8	60.4	05243	1.6	1.6	4G4	4.61	.26	7.32	9.65	166.00		1.65	1	24	25						





DDH: FAGU184

						-----ASSAYS-----															
DEPTHS	SAMPLE	INT.	REC.	ROCK	S.G.	CU	PB	ZN	AG(AA)	AG(FA)	AU(FA)	PC	PY	TOT	BAC	HG	MN	AS	BA	S.G.	
FROM	TO	NO.		UNIT	PULP	%	%	%	G/MT	G/MT	G/MT	%	%	FE	%	%	%	%	%	W.R.	
.0	2.7	14353	2.7	.7	4A0	.08	.78	1.44	17.00												
3.2	5.0	14354	1.8	1.8	4CA	.14	.57	1.71	13.00												
5.8	7.8	14355	2.0	2.0	4CA	.14	.61	.69	12.00												
7.8	9.8	14356	2.0	2.0	4CA	.08	.70	1.45	14.99												
9.8	11.8	14357	2.0	2.0	4CA	.05	.72	1.31	14.99												
11.8	13.8	14358	2.0	2.0	4ACD	3.16	.05	3.43	6.79	57.99		.47	1	5	7						
23.2	24.7	14359	1.5	.9	4A4		.07	2.52	4.38	38.00											
26.3	27.9	14360	1.6	1.3	4C0	2.97	.07	1.77	2.44	27.99		.47	2	3	6						
27.9	29.3	14361	1.4	1.3	4A0	3.00	.05	1.31	2.64	22.00		.47	1	4	6						
29.3	31.3	14362	2.0	1.9	4C5		.05	.56	1.08	11.00											
31.3	33.3	14363	2.0	2.0	4C5		.05	.70	.95	14.99											
33.3	35.8	14364	2.5	2.4	4C0		.05	.44	1.22	10.00											
35.8	37.6	14365	1.8	1.8	4A0		.07	.67	1.09	13.00											
37.6	39.6	14366	2.0	1.8	4C0		.04	.81	1.41	14.99											
39.6	41.6	14367	2.0	1.8	4C0		.02	.56	.82	11.00											
41.6	42.7	14368	1.1	.9	4C0		.05	.69	1.08	13.99											
42.7	44.7	14369	2.0	2.0	4C5		.05	.68	1.41	13.99											
44.7	46.7	14370	2.0	1.8	4C5		.05	.49	1.05	10.00											
46.7	49.0	14371	2.3	2.0	4C5		.05	.81	1.04	19.00											
50.5	51.8	14372	1.3	.7	4C0		.11	.42	.35	19.00											
51.8	53.8	14373	2.0	2.0	4A4	3.39	.05	6.34	8.80	95.00		.95	1	8	10						
53.8	55.8	14374	2.0	2.0	4A4	3.52	.08	4.29	10.50	73.00		.89	7	1	9						
55.8	57.9	14375	2.1	1.8	4A4	3.41	.16	4.55	9.59	75.00		1.16	1	11	12						
57.9	59.2	14376	1.3	1.3	4E4	4.40	.13	5.00	5.50	80.00		1.03	1	29	31						
64.3	66.1	14377	1.8	1.8	4E44	4.50	.11	7.20	14.30	124.99		.81	1	22	24						
66.1	67.8	14378	1.7	1.6	4E44	4.05	.05	11.00	16.39	148.00		1.37	2	13	15						
68.6	70.9	14379	2.3	1.5	4E4	3.60	.08	7.09	9.80	104.00		1.37	4	10	14						
98.0	100.6	14380	2.6	2.6	4ALC	3.14	.11	1.66	2.44	28.99		1.58	6	5	12						
107.8	109.0	14381	1.2	1.2	4A7		.08	1.85	2.37	27.99											
109.0	110.7	14382	1.7	1.5	4C5		.16	.75	.93	13.00											
110.7	111.9	14383	1.2	1.2	4C57		.28	.82	1.02	18.00											
111.9	113.4	14384	1.5	1.5	4E68	4.13	.24	2.60	4.08	48.00		.81	4	23	28						
113.4	114.5	14385	1.1	1.1	4C5	3.47	.46	1.37	1.64	27.99		.89	10	12	22						
114.5	117.1	14386	2.6	2.5	4AC		.16	.28	.20	3.99											
117.1	118.2	14387	1.1	1.1	4C5		.17	.66	.94	12.00											
118.2	119.3	14388	1.1	1.1	4ACD		.08	1.68	3.18	29.99											
122.4	124.4	14389	2.0	1.9	4E48	3.74	.17	1.30	1.74	23.00		.95	5	20	25						
124.4	126.4	14390	2.0	2.0	4CE8	3.76	.22	1.76	2.18	28.99		.62	5	21	26						
126.4	128.2	14391	1.8	1.8	4C58		.14	.52	.68	11.00											
128.2	130.7	14392	2.5	2.4	4A0		.16	.10	.17	9.00											
130.7	132.7	14393	2.0	2.0	4C0		.14	.14	.11	10.00											
132.7	134.0	14394	1.3	1.3	4A0		.26	.10	.20	10.00											
134.0	136.6	14395	2.6	2.6	4C7		.17	.69	1.04	17.00											
136.6	137.7	14396	1.1	1.1	4EG8	4.58	.16	4.06	5.40	56.99		.81	2	23	25						
137.7	140.0	14397	2.3	2.3	4C0		.20	.41	.71	13.00											
140.0	141.8	14398	1.8	1.8	4GE4	4.25	.19	4.34	5.70	58.99		.75	2	18	20						
141.8	143.5	14399	1.7	1.7	4GE4	4.63	.29	5.70	7.29	82.00		1.37		19	20						
143.5	146.5	14400	3.0	3.0	4A0	3.12	.02	.97	1.66	20.00		.27	3	8	11						











DDH: FAGU190

---DEPTHS---		SAMPLE NO.	INT.	REC.	ROCK UNIT	S.G. PULP	-----ASSAYS-----														S.G. W.R.
FROM	TO						CU %	PE %	ZN %	AG(AA) G/MT	AG(FA) G/MT	AU(FA) G/MT	PO %	PY %	TOT FE	BAO %	HG %	MN %	AS %	BA %	
4.5	6.5	12993	2.0	1.8	4C5		.04	.85	1.68	13.99											
6.5	8.5	12994	2.0	1.4	4C5		.05	.93	1.61	13.00											
8.5	10.6	12995	2.1	1.9	4C5	3.02	.04	1.66	1.81	21.00		.40		4	5						
10.6	12.1	12996	1.5	1.3	4C0	2.95	.02	2.54	2.29	34.00		.55		3	4						
12.1	13.7	12997	1.6	1.5	4C0	2.91	.02	2.29	1.81	29.99		1.23		2	3						
13.7	15.6	12998	1.9	1.9	4C5	2.91	.19	2.08	2.37	26.00		.20	2	3	6						
28.0	29.8	12999	1.8	1.6	4D0	2.93	.01	1.81	3.29	27.00		.27	1	1	3						
29.8	31.2	13000	1.4	1.3	4C5	2.91	.02	1.39	2.75	19.00		.27	1	2	3						
31.2	33.3	14125	2.1	2.1	4A0	3.00	.02	1.01	.46	19.00		.62	1	6	7						
33.3	34.9	14126	1.6	1.6	4C5	2.89	.02	1.05	1.70	17.00		.20	1	1	3						
34.9	36.5	14127	1.6	1.5	4C5	2.91	.05	.88	1.87	15.99		.20	1	1	3						
36.5	38.4	14128	1.9	1.7	5D4*		.04	.14	.19	6.00											
38.4	40.4	14129	2.0	1.8	4C0		.04	.29	.69	7.99											
40.4	42.4	14130	2.0	1.9	4C0		.05	.29	1.07	9.00											
42.4	44.4	14131	2.0	1.9	4C0		.04	.42	.52	10.00											
44.4	45.2	14132	.8	.6	4D0	3.14	.11	1.82	4.05	35.00		.34	1	7	8						
45.2	47.2	14133	2.0	2.0	4A0	3.31	.10	1.44	3.45	30.99		1.30	1	13	15						
47.2	48.7	14134	1.5	1.5	4A4	3.29	.05	4.25	8.50	62.99		.89	1	9	10						
48.7	50.7	14135	2.0	2.0	4A30	3.68	.17	1.15	1.46	31.99		1.10		22	22						
50.7	52.7	14136	2.0	1.8	4A30		.23	.62	1.25	25.00											
52.7	54.7	14137	2.0	1.9	4A30		.20	.81	1.34	27.99											
54.7	55.6	14138	.9	.9	4A30		.17	.57	.89	23.00											
55.6	57.8	14139	2.2	2.1	4E4	4.34	.20	4.65	5.90	84.00		1.58	1	27	29						
57.8	59.1	14140	1.3	1.3	4G4	4.73	.26	4.42	6.99	77.00		.62		22	23						
59.1	60.1	14141	1.0	1.0	4E46	4.75	.22	9.00	11.09	118.99		1.78	3	24	28						
60.1	61.5	14142	1.4	1.4	4C3	3.87	.29	1.87	1.46	36.00		.95	2	23	26						
61.5	63.7	14143	2.2	2.1	4E46	4.71	.16	6.20	10.09	97.00		1.16		19	20						
63.7	64.4	14144	.7	.7	4EG	4.87	.22	4.63	9.69	85.00		.68		24	25						
64.4	66.0	14145	1.6	1.5	4E0	4.88	.16	1.88	2.08	31.99		.62		38	39						
66.0	67.1	14146	1.1	1.1	4G4	4.79	.14	5.00	10.09	70.00		.81		16	17						
67.1	69.1	14147	2.0	1.6	4EG	4.63	.22	6.20	10.59	102.00		1.98		24	25						
69.1	71.1	14148	2.0	1.8	4EG	4.80	.22	4.29	6.90	81.00		1.43		29	30						
71.1	72.9	14149	1.8	1.7	4EG	4.92	.16	5.70	8.69	94.00		1.23	1	27	28						
72.9	74.1	14150	1.2	1.2	4E46	3.58	.04	2.60	3.10	39.00		.27	3	12	15						
74.1	76.1	14151	2.0	1.9	4G4	4.94	.23	7.20	10.30	110.99		1.85		27	28						
76.1	78.0	14152	1.9	1.8	4G4	4.95	.26	5.70	8.90	118.99		1.37		25	25						





































DDH: FAGU214

						-----ASSAYS-----															
---DEPTHS---	SAMPLE	INT.	REC.	ROCK	S.G.	CU	PB	ZN	AG(AA)	AG(FA)	AU(FA)	PO	PY	TOT	BAC	HG	MN	AS	BA	S.G.	
FROM	TO	NO.		UNIT	PULP	%	%	%	G/MT	G/MT	G/MT	%	%	FE	%	%	%	%	%	W.R.	
3.0	4.5	14330	1.5	1.5	4A34	3.43	.04	2.45	4.25	48.00		.55	12	1	13						
4.5	6.5	14331	2.0	2.0	4A34	3.35	.02	4.46	5.09	66.00		.68	8	1	9						
6.5	7.6	14332	1.1	1.0	5D4*	3.18	.02	1.49	2.20	23.00		.34	3	4	7						
7.6	9.1	14333	1.5	1.5	4D45	3.39	.05	3.75	8.50	62.99		.55	7	3	10						
9.1	12.3	14334	3.2	1.4	4D54	4.34	.02	3.95	9.30	66.00		.55	11	1	13						



DDH: FAGU216

						-----ASSAYS-----															
---DEPTHS---	SAMPLE	INT.	REC.	ROCK	S.G.	CU	PB	ZN	AG(AA)	AG(FA)	AU(FA)	PO	PY	TOT	BAG	HG	MN	AS	BA	S.G.	
FROM	TO	NO.		UNIT	PULP	%	%	%	G/MT	G/MT	G/MT	%	%	FE	%	%	%	%	%	W.R.	
.0	1.5	90785	1.5	.4	4A34		3.87	5.57	65.50												
1.5	3.0	90786	1.5	1.5	4A34		1.89	4.29	37.39												
3.0	4.6	90787	1.6	1.6	4A34		2.93	6.16	56.60												
4.6	6.1	90788	1.5	1.5	4A34		3.95	7.20	70.59												
6.1	7.6	90789	1.5	1.5	4A34		5.00	10.06	80.59												
7.6	9.1	90790	1.5	1.5	4A34		2.58	5.46	41.50												
9.1	10.7	90791	1.6	1.6	4A34		2.75	6.70	45.29												
10.7	12.5	90792	1.8	1.7	4A34		1.47	4.38	26.39												
35.1	36.6	90793	1.5	1.5	4E4		9.57	19.93	138.19												
36.6	38.1	90794	1.5	1.5	4E4		13.40	21.48	215.69												
38.1	39.6	90795	1.5	1.5	4E4		10.42	18.62	191.69												
46.1	48.1	90796	2.0	2.0	4D4		5.54	9.51	96.70												
49.8	51.8	90797	2.0	2.0	4D0		3.77	3.74	50.39												
51.8	53.3	90798	1.5	1.5	4A3		1.05	1.35	17.10												
62.8	64.0	90969	1.2	1.2	3G0		1.67	2.79	30.19												
64.0	65.5	90970	1.5	1.5	4E4S		5.00	6.29	77.79												
65.5	67.1	90971	1.6	1.6	4EA		4.15	6.92	61.39												
67.1	68.6	90972	1.5	1.4	4A1		2.23	2.04	28.49												
68.6	70.1	90973	1.5	1.4	4A1		1.55	1.83	20.19												
70.1	71.6	90974	1.5	1.3	4AE4		5.59	10.17	70.59												
71.6	73.6	90975	2.0	2.0	4EAL		3.49	6.25	52.50												
94.0	96.0	90976	2.0	1.9	4A0		.23	.34	5.09												
96.0	97.5	90977	1.5	1.5	4A0		.45	1.19	7.20												
97.5	99.1	90978	1.6	1.4	4A0		.08	.29	2.10												
100.6	102.1	90980	1.5	1.4	4A0		.17	.29	3.10												
103.6	105.2	90981	1.6	1.4	4A0		.08	.10	2.10												
105.2	106.7	90982	1.5	1.4	4A0		.08	.42	2.10												
106.7	108.2	90983	1.5	.5	4AE		3.87	7.33	45.29												
108.2	109.7	90984	1.5	1.0	4A0		.29	.88	5.09												
123.3	123.8	90985	.5	.5	4D34		9.40	9.30	90.90												
126.5	128.0	90986	1.5	1.5	4C8		1.87	1.92	18.19												
128.0	129.5	90987	1.5	1.5	4D8		2.75	2.35	30.19												

\*\*THIS REPORT WAS REQUESTED BY: LEEP .GEOLOGY AT: 13:44:01

> 90,000 ASSAYS - SAMPLE NUMBER

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK UNIT	CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT
		FROM	TO								
FAGA001	90000	262.5	263.3	.8	.0	5B21	.25	1.45	1.28	20.20	
FAGA004	90001	199.9	201.5	1.6	.0	4E4	.30	6.16	8.75		126.10
FAGA004	90002	201.5	203.0	1.5	.0	4E4	.29	7.50	10.10		126.10
FAGA004	90003	203.0	204.5	1.5	.0	4E4	.34	5.96	10.80		129.20
FAGA004	90004	204.5	205.9	1.4	.0	4E4	.30	7.19	13.98		151.20
FAGA004	90005	205.9	208.0	2.1	.0	4LD	.16	2.23	3.84		60.30
FAGA005	90006	160.5	161.7	1.2	.0	4E4	.25	6.50	21.50		113.80
FAGA005	90007	161.7	163.7	2.0	.0	4E4	.16	4.70	22.90		59.00
FAGA005	90008	163.7	165.4	1.7	.0	4E4	.32	9.20	15.50		176.20
FAGA005	90009	165.4	166.0	.6	.0	4E4	.06	.38	.38		9.60
FAGA005	90010	166.0	166.5	.5	.0	4E4	.05	3.98	8.06		61.00
FAGA005	90011	166.5	169.6	3.1	.0	5B2	.06	.38	.62		2.70
FAGA005	90012	169.6	170.5	.9	.0	4E4	.19	4.05	6.85		77.50
FAGA005	90013	170.5	171.8	1.3	.0	4E4	.16	6.45	12.30		104.90
FAGA005	90014	171.8	173.1	1.3	.0	4E4	.28	6.60	13.10		152.20
FAGA005	90015	173.1	174.3	1.2	.0	4E4	.29	5.78	9.24		149.50
FAGA005	90016	174.3	175.9	1.6	.0	4E4	.33	5.85	9.03		82.30
FAGA005	90017	175.9	177.1	1.2	.0	4E4	.34	6.90	9.10		142.60
FAGA005	90018	177.1	178.8	1.7	.0	4E4	.18	9.20	17.40		125.50
FAGA005	90019	178.8	180.4	1.6	.0	4AG	.05	1.13	2.28		16.50
FAGA009	90020	113.9	115.5	1.6	.0	4AL	.09	1.18	3.36		21.90
FAGA009	90021	115.5	117.0	1.5	.0	4L4	.03	.95	2.28		11.00
FAGA009	90022	117.0	118.5	1.5	.0	4A4	.03	2.23	5.28		62.40
FAGA009	90023	118.5	120.0	1.5	.0	4A4	.04	2.50	5.40		57.30
FAGA009	90024	120.0	121.6	1.6	.0	4LA	.05	2.03	4.20		38.40
FAGA009	90025	121.6	123.1	1.5	.0	4L1	.03	.98	1.40		19.20
FAGA009	90026	123.1	124.6	1.5	.0	4L1	.06	2.00	4.02		27.40
FAGA009	90027	132.3	133.8	1.5	.0	4A14	.08	2.85	6.12	57.60	
FAGA009	90028	133.8	135.3	1.5	.0	4A14	.12	5.55	10.52	96.00	
FAGA009	90029	135.3	136.9	1.6	.0	4A14	.09	7.50	10.63	95.30	
FAGA009	90030	136.9	138.4	1.5	.0	4A14	.10	7.35	11.88	103.20	
FAGA009	90031	138.4	139.9	1.5	.0	4A14	.05	2.45	5.16	74.70	
FAGA009	90032	139.9	141.5	1.6	.0	4A14	.04	1.90	4.26	55.50	
FAGA014	90033	192.6	193.2	.6	.0	4L24	.19	1.45	1.22	21.90	
FAGA014	90034	266.4	269.1	2.7	.0	4AG	.16	.29	.42		31.50
FAGA014	90035	269.1	273.1	4.0	.0	4AG	.16	.63	.69		37.00
FAGA014	90036	273.1	275.8	2.7	.0	4EG4	.30	6.53	6.96		91.50
FAGA014	90037	275.8	278.9	3.1	.0	4AG	.20	.55	.66		12.30
FAGA014	90038	278.9	281.9	3.0	.0	4AG	.17	2.00	2.76		53.50
FAGA014	90039	281.9	283.5	1.6	.0	4AG	.15	.33	.46		21.90
FAGA014	90040	283.5	287.1	3.6	.0	4EC	.20	1.73	2.00		32.90
FAGA068	90041	128.5	129.8	1.3	1.3	4E4		7.71	12.62		105.90
FAGA068	90042	188.7	190.2	1.5	1.5	4DC		3.30	4.80	40.40	
FAGA068	90043	203.5	205.2	1.7	1.6	4A4		8.00	7.80	110.00	
FAGA068	90044	205.2	206.8	1.6	1.6	4A4		8.15	15.38	121.00	
FAGA068	90045	206.8	208.0	1.2	1.2	4A4		3.30	5.22	64.50	
FAGA068	90046	215.3	217.4	2.1	2.1	4A4		7.63	9.81	102.80	
FAGA068	90047	217.4	219.3	1.9	1.9	4A4		10.23	19.00	141.20	
FAGA068	90048	219.3	219.9	.6	.6	4A4		10.06	12.46	121.00	
FAGA068	90049	241.0	242.4	1.4	1.3	4EG4		4.73	6.00	75.80	

DDH	SAMPLE	----DEPTHS----		INT	REC	ROCK UNIT	CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT
		FROM	TO								
FAGA068	90050	242.4	244.0	1.6	1.6	4EG4		5.10	8.30	70.60	
FAGA068	90051	247.5	249.5	2.0	2.0	4E4		5.63	10.47	75.80	
FAGA073	90052	35.7	36.7	1.0	.5	4AG		.54	1.04		8.90
FAGA073	90053	36.7	38.4	1.7	1.0	4AG		1.43	2.73		24.30
FAGA073	90054	38.4	39.3	.9	.6	4A4		1.60	3.42		32.20
FAGA073	90055	39.3	41.1	1.8	.7	4A4		1.83	4.32		35.30
FAGA073	90056	41.1	42.7	1.6	.8	4AG		1.38	1.30		27.40
FAGA073	90057	46.0	46.9	.9	.8	4E4		3.60	9.54		66.50
FAGA073	90058	75.3	77.1	1.8	1.7	5C3		.35	.42		3.10
FAGA073	90059	77.1	79.9	2.8	2.7	4E4		8.86	14.93		128.20
FAGA073	90060	79.9	81.4	1.5	1.5	4D4		4.20	5.28		58.60
FAGA073	90061	81.4	84.4	3.0	3.0	4D4		3.45	7.32		50.40
FAGA073	90062	84.4	86.4	2.0	2.0	4D4		4.13	7.30		55.50
FAGA073	90063	86.4	88.1	1.7	1.7	4D4		1.95	5.76		25.40
FAGA073	90064	88.9	90.5	1.6	1.2	4A4		2.15	4.86		32.20
FAGA073	90065	90.5	92.4	1.9	1.8	4A4		2.08	3.48		28.10
FAGA073	90066	92.4	94.2	1.8	1.8	4A4		5.93	12.58		90.80
FAGA073	90067	94.2	95.3	1.1	.7	4A4		2.78	5.16		44.20
FAGA073	90068	95.3	97.4	2.1	.9	4A4		2.93	7.68		46.30
FAGA073	90069	98.6	99.5	.9	.4	5C@4		1.00	4.26		18.20
FAGA073	90070	100.1	100.6	.5	.5	5C@4		2.40	7.02		39.40
FAGA073	90071	100.6	103.5	2.9	2.9	4D4		5.84	10.45		88.80
FAGU114	90072	22.9	24.4	1.5	1.5	4A4		2.33	3.85	35.30	
FAGU005	90073	44.2	48.7	4.5	.0	4A14		1.95	3.78	37.80	
FAGU006	90074	.0	2.4	2.4	.4	4A14		2.85	3.65	40.50	
FAGU006	90075	6.0	9.1	3.1	2.9	4A14		2.28	4.58	34.30	
FAGU006	90076	14.4	15.2	.8	.8	4A14		.95	2.70	15.40	
FAGU009	90077	31.0	32.0	1.0	.5	3G46		2.10	2.00		35.30
FAGU009	90078	32.0	33.0	1.0	1.0	4L4		2.20	2.98		34.30
FAGU009	90079	38.1	39.5	1.4	.0	3G4		.33	1.10		4.10
FAGU016	90080	60.3	61.1	.8	.8	10Q0		.75	1.05	17.10	
FAGU025	90081	59.4	61.0	1.6	1.2	4DG		2.18	3.10	42.51	
FAGU027	90082	94.7	96.0	1.3	.8	4L4		2.23	3.60	33.30	
FAGU027	90083	99.1	100.6	1.5	1.1	4A1		1.20	2.35	18.20	
FAGU027	90084	100.6	102.1	1.5	1.1	4A14		2.80	3.30	34.30	
FAGU027	90085	102.1	103.5	1.4	1.0	4A1		.90	2.33		12.00
FAGU004	90086	6.9	10.6	3.7	.0	4A24		2.98	4.95	40.50	
FAGU004	90087	10.6	14.2	3.6	.0	4A24		2.68	4.63	38.40	
FAGU004	90088	14.2	14.9	.7	.0	4A2		1.13	2.10	19.20	
FAGU004	90089	14.9	15.5	.6	.0	4A24		2.40	3.80	39.40	
FAGA021	90090	100.1	101.1	1.0	.9	5B20	.02	.03	.10		
FAGA021	90091	101.1	103.5	2.4	2.0	4E4	.08	5.78	11.35		79.50
FAGA021	90092	103.5	104.3	.8	.7	5D4*	.02	.10	.30		
FAGA021	90093	104.3	107.1	2.8	2.1	4AE4	.15	8.25	14.83		149.50
FAGA021	90094	107.1	109.4	2.3	1.8	4AL	.03	2.23	4.26		32.20
FAGA021	90095	109.4	112.4	3.0	1.9	4A4	.06	4.43	8.76		56.20
FAGA021	90096	112.4	113.7	1.3	1.3	4LA4	.06	3.75	1.44		39.80
FAGA021	90097	113.7	115.2	1.5	1.4	4A4	.05	4.20	1.50		45.90
FAGA021	90098	115.2	117.4	2.2	2.2	4AG	.08	.68	1.74		9.60
FAGA021	90099	117.4	119.1	1.7	1.7	4AG	.08	.64	1.66		9.60

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK UNIT	CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT
		FROM	TO								
FAGA021	90100	119.1	121.1	2.0	2.0	4L34	.10	.70	1.34		11.00
FAGA021	90101	121.1	123.2	2.1	1.7	4L34	.08	.63	1.14		10.30
FAGA021	90102	132.3	133.8	1.5	1.5	5B6	.02	.03	.05		
FAGA021	90103	167.0	168.6	1.6	1.4	5B26	.02	.08	.33		
FAGA021	90104	179.8	181.2	1.4	1.4	4L0	.03	.08	.10		8.90
FAGA021	90105	181.2	183.3	2.1	2.0	4EA4	.12	2.43	4.74		42.50
FAGA021	90106	183.3	185.3	2.0	1.7	4E4	.09	3.08	5.04		48.00
FAGA021	90107	185.3	186.8	1.5	1.5	4E4	.09	2.50	4.20		52.10
FAGA021	90108	186.8	189.9	3.1	3.1	4E4	.12	4.43	8.76		71.30
FAGA021	90109	189.9	192.9	3.0	3.0	4EG4	.04	4.28	9.12		76.80
FAGA021	90110	192.9	194.5	1.6	1.6	4EG4	.17	5.03	9.36		83.60
FAGA021	90111	194.5	196.0	1.5	1.5	4E4	.17	6.83	11.50		128.90
FAGA021	90112	196.0	197.5	1.5	1.5	4E4	.15	2.25	4.26		51.40
FAGA060	90113	116.3	116.6	.3	.3	4L0		.68	.51	19.20	
FAGA060	90114	259.7	262.1	2.4	2.1	5B6		.07	.04		
FAGA060	90115	339.7	340.2	.5	.5	5B26		1.63	.66		27.40
FAGA013	90117	44.0	48.3	4.3	4.3	4G4	.16	8.10	8.40		107.00
FAGA013	90118	48.3	52.3	4.0	4.0	4G4	.19	7.65	5.52		92.60
FAGA013	90119	54.9	59.0	4.1	4.1	4E0	.21	5.03	4.20		91.90
FAGA013	90120	59.0	60.1	1.1	1.1	4E0	.15	1.50	1.90		29.50
FAGA013	90121	60.1	61.6	1.5	1.5	4E4	.20	5.25	5.40		71.30
FAGA013	90122	61.6	64.2	2.6	2.6	4KC	.08	1.25	.16		33.90
FAGA013	90123	64.2	66.8	2.6	2.6	4KC	.20	1.63	.90		53.50
FAGA013	90124	121.3	123.1	1.8	1.8	5A0	.03	.90	2.00		24.70
FAGA017	90125	232.0	235.0	3.0	3.0	4E71	.30	2.00	1.58		34.30
FAGA017	90126	235.0	237.1	2.1	2.1	4E71	.22	.30	.30		11.00
FAGA017	90127	237.1	239.0	1.9	1.9	4G4	.23	6.38	7.92		87.80
FAGA023	90134	221.9	224.3	2.4	.0	4L0		.03	.03		2.10
FAGA023	90135	245.2	246.9	1.7	.0	4L0		.32	.76		5.10
FAGA055	90136	174.7	175.2	.5	.0	5B6		1.08	2.76		17.10
FAGA096	90138	148.4	149.1	.7	.0	4D4		9.63	22.37	177.60	
FAGA096	90139	149.1	150.3	1.2	.0	4D4		7.53	17.61	125.10	
FAGA096	90140	150.3	151.5	1.2	.0	4D4		7.20	17.92	142.30	
FAGA070	90141	61.4	62.0	.6	.0	4A4		4.58	8.00	60.30	
FAGA070	90142	79.2	81.7	2.5	.0	4LA		1.88	4.38	30.20	
FAGA070	90143	64.8	66.6	1.8	.0	4AE4		6.59	14.70	112.80	
FAGU003	90144	64.0	65.4	1.4	1.2	4LD		1.00	1.30		15.09
FAGU003	90145	65.4	66.7	1.3	1.3	4LD		7.04	5.65		88.80
FAGA088	90146	116.4	118.1	1.7	1.5	4EA4		5.70	9.55		79.50
FAGA088	90147	118.1	120.1	2.0	1.5	4EA4		2.00	3.90		22.30
FAGA088	90148	204.1	204.8	.7	.3	4A4		4.28	6.55		57.60
FAGA088	90149	204.8	205.7	.9	.8	4DE4		5.68	8.77		80.60
FAGA088	90150	205.7	208.0	2.3	2.3	4DE4		7.87	10.83		103.90
FAGA088	90151	208.0	208.8	.8	.6	4DE4		5.03	5.40		57.60
FAGA088	90152	209.4	210.0	.6	.5	4DE4		5.64	6.24		67.50
FAGA088	90153	327.4	329.2	1.8	1.8	4L2		.13	.37		4.10
FAGA157	90154	67.6	70.7	3.1	.6	4LEA		1.00	.60		13.00
FAGA066	90155	68.3	70.0	1.7	.0	4A4		2.10	4.44	23.30	
FAGA066	90156	88.6	89.5	.9	.0	4A34		5.63	5.52	61.40	

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK UNIT	CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT
		FROM	TO								
FAGA066	90157	106.2	107.2	1.0	.0	4DEA4		4.65	5.82	54.40	
FAGA066	90158	156.4	158.2	1.8	.0	4E#4		1.75	3.00	25.40	
FAGA066	90159	158.2	159.6	1.4	.0	4E#4		5.70	7.20	72.70	
FAGA045	90160	50.9	51.8	.9	.9	4B0		.73	3.18	9.90	
FAGA153	90161	58.3	60.0	1.7	1.7	4AC		1.18	1.40		15.10
FAGA045	90162	66.4	67.2	.8	.6	10Q0		2.30	4.42	19.20	
FAGA045	90163	177.7	178.8	1.1	.9	5D4*		1.48	.86	19.20	
FAGA052	90164	78.0	78.3	.3	.2	5B69		11.00	20.45	171.40	
FAGA052	90165	85.0	85.9	.9	.6	5B69		1.75	2.22	27.40	
FAGA052	90166	86.1	87.6	1.5	.0	4DGL		8.18	10.72	110.00	
FAGU100	90170	80.2	82.0	1.8	1.6	4A4		2.20	5.20		31.20
FAGA134	90171	65.7	66.4	.7	.7	5B9		1.20	1.40	17.10	
FAGA134	90172	66.4	67.9	1.5	1.5	4G41		7.56	9.70	99.80	
FAGA147	90173	136.2	137.8	1.6	1.6	4L0		.22	.53		3.09
FAGA147	90174	159.0	160.7	1.7	1.5	5A1		.07	.20		3.09
FAGA021	90175	197.5	198.7	1.2	1.2	4A4	.12	5.18	9.00		45.30
FAGA083	90176	240.4	241.1	.7	.7	4A1		.10	.46		5.10
FAGA132	90177	93.2	94.5	1.3	1.3	4L0		.70	1.65		7.20
FAGA132	90178	133.4	134.9	1.5	1.5	4A4		4.48	10.56	74.70	
FAGA019	90179	102.4	103.8	1.4	1.4	4C0	.22	1.85	1.92		47.30
FAGA019	90180	103.8	105.3	1.5	1.5	4C0	.13	1.18	1.02		11.00
FAGA019	90181	105.3	108.2	2.9	2.9	4CG4	.11	6.68	5.64		109.00
FAGA019	90182	134.7	135.9	1.2	1.2	5AD	.02	.05	.17		1.40
FAGA019	90183	137.8	139.6	1.8	1.8	4A13	.17	1.15	2.00	31.50	
FAGA019	90184	139.6	142.4	2.8	2.8	4E0	.34	.38	.60	21.90	
FAGA019	90185	142.4	145.5	3.1	3.0	4E04	.07	7.35	9.36		139.90
FAGA019	90186	145.5	147.8	2.3	2.3	4C0	.18	.25	.82		14.40
FAGA019	90187	147.8	150.3	2.5	2.5	4C0	.14	2.28	1.60		34.30
FAGA019	90188	150.3	152.4	2.1	2.1	4A13	.06	4.95	6.96		60.30
FAGA019	90189	161.9	163.7	1.8	.3	4L14	.11	2.25	4.68		58.30
FAGA019	90190	163.7	164.6	.9	.5	4E4	.23	4.35	6.84		56.20
FAGA019	90191	164.6	165.5	.9	.8	4E4	.21	7.55	12.72		111.80
FAGA019	90192	165.5	166.7	1.2	1.2	4E4	.11	3.15	4.74		50.10
FAGA019	90193	166.7	168.2	1.5	1.2	4E4	.11	2.05	3.72		38.40
FAGA019	90194	168.2	169.8	1.6	1.6	4E4	.10	2.28	3.90		53.50
FAGA019	90195	169.8	171.3	1.5	1.5	4E4	.10	2.50	6.24		52.10
FAGA019	90196	171.3	172.8	1.5	1.5	4E4	.18	4.50	9.48		76.80
FAGA019	90197	172.8	174.4	1.6	1.6	4E4	.25	4.74	8.64		76.80
FAGA019	90198	174.4	175.9	1.5	1.5	4E4	.17	5.78	10.20		109.70
FAGA019	90199	175.9	176.7	.8	.8	4E4	.05	3.08	5.76		67.90
FAGA019	90200	176.7	177.8	1.1	1.1	4L14	.03	1.85	3.33		46.60
FAGA019	90201	194.2	197.2	3.0	2.9	4D45	.20	9.15	15.36		137.80
FAGA019	90202	197.2	198.4	1.2	1.2	4E1	.29	1.90	2.88		27.40
FAGA019	90203	198.4	200.9	2.5	2.5	4E14	.26	5.70	9.49		90.50
FAGA019	90204	200.9	202.5	1.6	1.6	4E14	.33	2.70	3.30		50.70
FAGA019	90205	202.5	205.3	2.8	2.8	4E14	.29	2.93	4.14		55.90
FAGA019	90206	207.6	208.4	.8	.8	4A13	.42	.08	.37	16.50	
FAGU007	90207	10.7	11.2	.5	.0	4A14		3.40	1.53	46.30	
FAGU007	90208	15.2	19.8	4.6	.4	4A14		2.93	2.43	45.30	
FAGU007	90209	19.8	21.4	1.6	1.6	4A1		.39	.90	8.90	

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK UNIT	CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT
		FROM	TO								
FAGU007	90210	21.4	23.0	1.6	1.5	4A1		.68	1.00	11.00	
FAGU007	90211	32.0	35.0	3.0	.0	4L24		1.65	2.45		28.50
FAGU007	90212	35.0	35.7	.7	.0	4L12		3.38	5.09		56.60
FAGU007	90213	53.8	54.7	.9	.8	4E4		7.39	12.72		128.20
FAGU007	90214	54.7	56.1	1.4	1.4	4A13		3.00	4.00		44.20
FAGA056	90215	104.0	106.1	2.1	.2	F		1.98	3.54	30.20	
FAGA056	90216	185.5	186.0	.5	.5	4L04		1.08	1.80	15.10	
FAGU018	90217	57.6	58.1	.5	.0	4L0		.75	1.05		17.14
FAGU018	90218	79.9	80.4	.5	.0	4A14		3.30	4.00	45.30	
FAGU022	90219	3.0	4.6	1.6	1.6	4A1		1.63	2.03	24.30	
FAGU022	90220	10.7	12.2	1.5	1.5	4A1		3.40	1.25	37.40	
FAGU022	90221	21.3	22.2	.9	.9	4A1		2.20	.93	24.30	
FAGU022	90222	22.2	22.9	.7	.7	4A14		4.00	2.20	50.40	
FAGU023	90223	.0	1.9	1.9	.6	4A1		2.03	2.55		24.30
FAGU023	90224	22.3	23.9	1.6	1.5	4A1		1.94	2.50		15.10
FAGU023	90225	67.1	67.8	.7	.7	4A1		.48	.93	16.10	
FAGU086	90226	84.0	85.3	1.3	1.3	4L3		.78	.52		9.90
FAGA062	90227	166.0	167.0	1.0	.0	4L4		1.12	1.14		12.00
FAGU088	90228	44.2	45.7	1.5	.0	4E4		5.65	7.90		79.50
FAGU088	90229	54.6	56.2	1.6	.0	4L34		2.83	4.15	41.50	
FAGU098	90232	.0	2.0	2.0	.0	4E0		4.75	8.61		70.60
FAGU098	90233	2.0	3.8	1.8	.0	4D4		8.37	19.67		145.00
FAGU098	90234	3.8	5.8	2.0	.0	4D4		9.17	23.91		152.20
FAGU098	90235	5.8	8.1	2.3	.0	4LE		2.10	4.65		43.50
FAGU098	90236	8.1	10.2	2.1	.0	4E4		7.02	9.74		121.00
FAGU098	90237	10.2	12.6	2.4	.0	4DL		5.46	11.55		76.80
FAGU098	90238	12.6	14.2	1.6	.0	4EK		3.10	4.05		46.30
FAGU098	90239	14.2	15.6	1.4	.0	4E4		5.26	7.44		94.60
FAGU098	90240	15.6	17.1	1.5	.0	4A4		2.68	4.70		45.30
FAGU098	90241	17.1	18.3	1.2	.0	4AC		1.13	1.78		14.10
FAGU098	90242	21.5	22.9	1.4	.0	4AC		.68	1.30		9.90
FAGU098	90243	22.9	23.4	.5	.0	4AC		.73	.75		18.20
FAGU098	90244	23.4	25.9	2.5	.0	4AC		1.80	2.80		29.10
FAGU098	90245	25.9	27.4	1.5	.0	4A4		3.78	7.05		46.30
FAGU102	90246	27.4	29.0	1.6	.0	4L4		2.58	4.00		44.20
FAGU102	90247	29.0	33.5	4.5	.0	4L4		2.58	4.40		35.30
FAGU102	90248	37.9	39.2	1.3	.0	4DL		2.48	6.25	27.40	
FAGU106	90249	15.2	16.8	1.6	.0	4AC		.30	.45		6.20
FAGU106	90250	97.5	100.0	2.5	.0	4LD		.78	.53		9.90
FAGU106	90251	125.3	127.5	2.2	.0	5A9		.13	.25		
FAGU106	90252	127.5	129.9	2.4	.0	5A9		.10	.13		
FAGU111	90253	83.4	85.3	1.9	.0	4L12		.10	.30		2.10
FAGU111	90254	86.8	88.3	1.5	.0	4L2		.38	.25		7.20
FAGU111	90255	88.3	89.8	1.5	.0	4L21		.05	.03		3.10
FAGU111	90256	105.8	107.5	1.7	.0	4L		.02	.10		
FAGU113	90257	66.1	66.9	.8	.0	4L0		.74	.64		9.10
FAGU121	90258	30.5	32.0	1.5	.0	4C0		.38	.78		9.90
FAGU121	90259	37.8	40.5	2.7	.0	4LC		.28	.50		8.20
FAGA035	90260	325.6	327.2	1.6	.0	5A9		.13	.06		5.10

DDH	SAMPLE	---DEPTHS---	INT	REC	ROCK	CU	PB	ZN	AG(AA)	AG(FA)
		FROM TO			UNIT	%	%	%	G/MT	G/MT
FAGA035	90261	328.0 328.6	.6	.6	5A9		1.10	1.18		23.30
FAGU149	90262	97.4 100.0	2.6	.0	4L72		.73	.68		14.10
FAGU150	90263	92.5 94.5	2.0	.0	4A0		1.53	2.78		23.30
FAGU156	90264	63.9 65.4	1.5	.0	5A6		1.65	2.88		38.40
FAGA163	90265	43.0 45.4	2.4	.0	4A0		1.20	2.38	16.10	
FAGA069	90266	334.9 337.0	2.1	.0	4L2		.82	1.56		14.10
FAGA069	90267	339.5 342.6	3.1	.0	4L2		.62	1.11		12.00
FAGA069	90268	350.8 352.3	1.5	.0	4L1		.23	.25		2.10
FAGA024	90269	139.8 142.8	3.0	.0	4G4	.13	6.15	5.40		90.80
FAGA024	90270	142.8 143.4	.6	.0	4DE	.17	1.25	.74		20.20
FAGA024	90271	143.4 144.7	1.3	.0	4EL	.03	.07	.08		
FAGA024	90272	144.7 146.0	1.3	.0	4E4	.15	5.55	3.54		86.70
FAGA024	90273	146.0 147.4	1.4	.0	4L5	.03	.18	.04		4.10
FAGA024	90274	147.4 150.4	3.0	.0	4D4	.18	7.20	6.12		97.70
FAGA024	90275	150.4 150.9	.5	.0	4L0	.04	.65	.68		9.30
FAGA024	90276	177.4 177.9	.5	.0	5A3	.03	.78	1.50		3.10
FAGA024	90277	177.9 178.6	.7	.0	5A3	.03	.08	.11		2.10
FAGA024	90278	180.1 182.0	1.9	.0	4A4	.10	2.13	3.72		35.30
FAGA024	90279	182.0 185.0	3.0	.0	4A4	.12	7.20	10.20		102.80
FAGA024	90280	185.0 187.3	2.3	.0	4A4	.20	3.83	7.56		75.80
FAGA024	90281	187.3 188.4	1.1	.0	4A4	.04	2.40	4.50		37.40
FAGA024	90282	188.4 189.1	.7	.0	4A0	.04	.85	1.74		16.10
FAGA024	90283	189.1 191.9	2.8	.0	5D4	.05	.19	.50		5.10
FAGA024	90284	191.9 194.2	2.3	.0	4A4	.13	8.25	14.63		111.10
FAGA024	90285	194.2 196.1	1.9	.0	4A4	.21	4.13	7.92		64.50
FAGA024	90286	196.1 197.6	1.5	.0	4A4	.10	3.83	6.96		60.30
FAGA024	90287	197.6 199.4	1.8	.0	4A4	.15	2.35	5.64		37.40
FAGA024	90288	199.4 201.0	1.6	.0	4A4	.05	2.85	4.92		39.40
FAGA024	90289	201.0 203.1	2.1	.0	4A4	.08	5.70	6.24		60.30
FAGA024	90290	203.1 204.2	1.1	.0	4A4	.15	4.05	2.76		57.60
FAGA024	90291	218.5 219.4	.9	.0	4A0	.07	1.65	2.34	15.10	
FAGA024	90292	219.4 221.3	1.9	.0	4A4	.15	2.05	3.18	31.20	
FAGA024	90293	221.3 223.1	1.8	.0	4A4	.12	2.50	3.54	32.20	
FAGA024	90294	223.1 223.4	.3	.0	4E4	.10	2.50	3.24	42.50	
FAGA024	90295	223.4 224.6	1.2	.0	4A0	.06	.72	.98		15.10
FAGA024	90296	224.6 226.2	1.6	.0	5A1	.03	.03	1.06		1.00
FAGA024	90297	226.2 226.6	.4	.0	5A1	.02	.25	.41		3.10
FAGA024	90298	226.6 228.0	1.4	.0	4L0	.50	.37	1.60		9.90
FAGA024	90299	228.0 228.9	.9	.0	4L0	.50	2.15	3.90		60.30
FAGA024	90300	228.9 229.5	.6	.0	4L0	.50	2.50	4.92		70.60
FAGA024	90301	229.5 229.8	.3	.0	4L0	.50	.08	.34		3.10
FAGA024	90302	229.8 231.0	1.2	.0	4C0	.50	4.65	8.52		96.70
FAGA024	90303	231.0 233.8	2.8	.0	5A3	.50	.13	.19		4.10
FAGA024	90304	249.6 251.8	2.2	.0	5A3	.50	.05	.11		2.10
FAGA024	90305	253.5 254.9	1.4	.0	5A1	.50	.05	.10		1.00
FAGA024	90306	254.9 257.3	2.4	.0	0Q0	.50	1.28	2.28		35.30
FAGA024	90307	343.6 345.2	1.6	.0	5B6	.50	.08	.13		2.10
FAGA004	90308	146.8 149.8	3.0	.0	5B46	.04	.10	.16		2.10
FAGA004	90309	157.0 160.6	3.6	.0	5B2	.08	.30	.25		4.10
FAGA005	90310	155.9 159.0	3.1	.0	5B26	.04	.20	.31		.21

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK UNIT	CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT
		FROM	TO								
FAGU116	90311	5.4	7.1	1.7	.8	5A69		.02	.05	1.03	
FAGA011	90342	123.9	127.7	3.8	.0	4LG	.21	1.95	1.26		38.40
FAGA011	90343	135.9	138.2	2.3	.0	4LH	.03	.28	.27		7.50
FAGA011	90344	150.4	152.4	2.0	.0	4EL4	.15	4.88	3.84		32.90
FAGA011	90345	152.4	154.2	1.8	.0	4EL4	.20	4.20	3.90		26.70
FAGA011	90346	178.0	180.3	2.3	.0	4GE4	.15	6.00	9.40		112.40
FAGA011	90347	180.2	182.6	2.4	.0	4G4	.20	8.74	13.50		156.30
FAGU035	90348	51.0	52.1	1.1	1.1	4A96		2.58	5.87		41.50
FAGU039	90349	4.1	6.2	2.1	2.1	5C4*		.14	.08	3.10	
FAGU045	90350	61.5	62.5	1.0	.0	4L2					
FAGU084	90351	6.3	10.2	3.9	3.5	4L0		.05	.14		.30
FAGU084	90352	12.4	13.1	.7	.6	4L3		.10	2.10		2.10
FAGU084	90353	16.7	17.1	.4	.4	4L0		.05	.22		2.10
FAGA099	90357	62.4	64.0	1.6	1.6	4A4		1.33	4.38		21.30
FAGA139	90358	121.1	122.5	1.4	1.1	4LG		.03	.08		1.00
FAGA084	90367	215.6	216.7	1.1	.0	4L14		3.08	4.86	45.30	
FAGA084	90368	216.7	219.2	2.5	.0	4G4		5.63	8.88	91.90	
FAGA084	90369	253.4	254.6	1.2	.0	5B49		1.30	1.84	20.20	
FAGA084	90370	254.6	255.8	1.2	.0	4E47		4.93	5.10	54.50	
FAGA072	90371	154.3	156.4	2.1	.0	4AE		9.53	18.11	126.10	
FAGA072	90372	156.4	156.7	.3	.0	4AE		5.64	12.45	79.50	
FAGA072	90373	160.9	162.0	1.1	.0	4A34		2.15	4.20	30.20	
FAGA072	90374	185.5	186.2	.7	.0	4A4		4.73	4.98	82.60	
FAGA082	90375	333.3	334.8	1.5	.0	4E81		2.20	3.78		23.30
FAGA082	90376	334.8	336.3	1.5	.0	4C78		1.45	2.73		18.20
FAGA082	90377	114.3	115.8	1.5	.0	4A4		1.63	3.60		33.30
FAGA087	90390	163.6	165.0	1.4	1.4	4D4		5.37	9.26	81.60	
FAGA087	90391	165.0	165.7	.7	.6	4D4		4.35	5.60	70.60	
FAGA087	90392	165.7	166.4	.7	.7	4A4		2.93	3.12	45.30	
FAGA087	90393	178.7	179.6	.9	.9	4A4		3.45	5.64	55.50	
FAGA087	90394	199.2	202.2	3.0	2.9	4D5		3.00	4.26	41.50	
FAGA087	90395	202.2	203.0	.8	.8	4D5		2.00	2.22	26.40	
FAGA087	90396	203.0	206.0	3.0	3.0	4D5		3.08	3.90	43.50	
FAGA087	90397	219.9	222.8	2.9	2.9	4D0		3.90	3.48	75.80	
FAGA087	90398	222.8	225.7	2.9	2.9	4D0		2.38	6.66	42.50	
FAGA087	90399	229.8	232.0	2.2	2.1	4D4		4.20	8.36	75.80	
FAGA087	90400	232.0	233.5	1.5	1.5	4D0		2.08	7.26	45.30	
FAGA087	90401	237.3	239.3	2.0	1.9	4E4		7.33	14.54	112.40	
FAGA087	90402	317.6	319.4	1.8	1.8	4GE4		4.13	6.15	82.60	
FAGA087	90403	319.4	320.9	1.5	1.4	4GE4		4.80	7.70	111.10	
FAGA087	90404	320.9	322.6	1.7	1.7	4GE		3.15	5.16	52.40	
FAGA087	90405	322.6	323.0	.4	.3	4E0		2.78	.50	50.40	
FAGA087	90406	323.7	324.1	.4	.4	4E0		.11	.04	4.20	
FAGA087	90407	324.1	326.9	2.8	2.8	4G4		4.28	5.28	71.70	
FAGA087	90408	326.9	327.5	.6	.6	4E0		.73	.28	21.30	
FAGA087	90409	328.8	330.6	1.8	1.7	4A4		5.71	6.48	85.70	
FAGA087	90410	330.6	331.9	1.3	1.3	4GE4		4.58	7.68	72.70	

DDH	SAMPLE	----DEPTHS----		INT	REC	ROCK UNIT	CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT
		FROM	TO								
FAGA087	90411	331.9	335.0	3.1	3.0	4GE4		4.73	8.48	85.70	
FAGA087	90412	335.0	337.0	2.0	1.9	4A34		4.65	10.07	95.60	
FAGA087	90413	337.0	337.6	.6	.6	4AL		.75	1.42	14.10	
FAGA085	90414	196.9	198.9	2.0	.0	4C0		.25	.62	6.20	
FAGA085	90415	198.9	201.9	3.0	.0	4C0		.40	1.08	8.90	
FAGA085	90416	201.9	205.0	3.1	.0	4C5		.83	.94	13.00	
FAGA085	90417	205.0	208.0	3.0	.0	4C5		.43	.68	5.10	
FAGA085	90418	208.0	211.1	3.1	.0	4C5		.44	1.14	6.20	
FAGA085	90419	211.1	214.1	3.0	.0	4C0		.44	1.10	5.10	
FAGA085	90420	214.1	217.2	3.1	.0	4C0		.80	1.16	12.00	
FAGA085	90421	217.2	218.8	1.6	.0	4D0		2.48	5.82	34.30	
FAGA085	90422	219.9	221.9	2.0	.0	3G0		.19	.33	1.00	
FAGA085	90423	221.9	224.5	2.6	.0	3G0		.22	.48	2.10	
FAGA085	90424	258.0	261.1	3.1	.0	4C0		.60	1.10	9.90	
FAGA085	90425	261.1	262.7	1.6	.0	4C0		.38	.61	7.20	
FAGA085	90426	262.7	264.6	1.9	.0	4A4		3.83	3.96	47.30	
FAGA085	90427	264.6	266.2	1.6	.0	4A4		2.38	3.72	30.20	
FAGA085	90428	266.2	268.6	2.4	.0	4A4		4.73	5.40	65.50	
FAGA085	90429	268.6	270.6	2.0	.0	4A0		.98	1.68	17.10	
FAGA085	90430	270.6	273.6	3.0	.0	4C0		.34	.28	6.20	
FAGA085	90431	273.6	277.7	4.1	.0	4A0		1.20	1.42	23.30	
FAGA085	90432	281.6	284.7	3.1	.0	4A30		1.38	1.40	21.30	
FAGA085	90433	292.9	296.0	3.1	.0	4A4		4.13	3.96	45.30	
FAGA085	90434	299.3	302.8	3.5	.0	4A4		2.78	2.82	36.30	
FAGA085	90435	338.1	340.9	2.8	.0	4D4		4.43	6.75	65.50	
FAGA085	90436	340.9	343.8	2.9	.0	4D43		5.25	6.96	65.50	
FAGA085	90437	343.8	346.3	2.5	.0	4D43		5.23	11.53	80.60	
FAGA085	90438	346.3	347.5	1.2	.0	4D43		4.85	7.48	64.50	
FAGA085	90439	348.1	351.1	3.0	.0	4D43		5.98	9.03	80.60	
FAGA085	90440	351.1	352.3	1.2	.0	4E4		4.54	7.68	55.50	
FAGA085	90441	357.0	357.8	.8	.0	4D45		6.35	9.97	90.80	
FAGA085	90442	360.6	361.6	1.0	.0	4D0		3.87	4.62	61.40	
FAGA085	90443	366.5	368.5	2.0	.0	4L57		.43	.26	7.20	
FAGA085	90444	368.5	369.1	.6	.0	4L57		.65	1.13	14.10	
FAGA085	90445	390.8	391.5	.7	.0	4A0		.63	1.06	8.90	
FAGA085	90446	391.5	392.4	.9	.0	4E47		5.12	3.96	50.70	
FAGA085	90447	393.5	395.2	1.7	.0	4E4		4.65	3.66	51.40	
FAGA085	90448	400.2	400.7	.5	.0	4E80		2.78	2.76	35.30	
FAGA085	90449	239.6	242.8	3.2	.0	4D5		3.00	3.96	36.30	
FAGA089	90450	343.0	344.4	1.4	.0	4A0		.05	.36	1.00	
FAGA089	90451	344.4	347.7	3.3	.0	4A0		.21	.38	8.20	
FAGA089	90452	347.7	349.8	2.1	.0	4C0		.03	.03	1.00	
FAGA089	90453	352.7	356.7	4.0	.0	4A0		.08	.14	3.10	
FAGA089	90455	356.7	357.6	.9	.0	4C0		.09	.16	1.00	
FAGA089	90456	377.2	378.0	.8	.8	4E0		.70	.52	19.20	
FAGA093	90457	289.3	289.7	.4	.0	4E4		4.88	4.56	75.80	
FAGA093	90458	289.7	290.8	1.1	.0	4L12		4.88	4.56	75.80	
FAGA089	90459	163.7	165.5	1.8	.0	4CE		.93	1.74	15.10	
FAGA089	90460	165.5	168.0	2.5	.0	4EC		1.13	1.14	22.30	
FAGA089	90461	259.0	260.7	1.7	.0	4D4#5		5.03	9.50	72.70	

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK UNIT	CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT
		FROM	TO								
FAGA075	90462	26.2	27.7	1.5	1.5	4A4		2.28	5.58	40.40	
FAGA075	90463	27.7	29.0	1.3	1.3	4A4		1.60	3.84	26.10	
FAGA075	90464	29.0	30.5	1.5	1.5	4A4		2.00	4.02	31.20	
FAGA075	90465	30.5	32.6	2.1	2.1	4A4		1.85	3.90	30.20	
FAGA075	90466	32.6	35.1	2.5	2.5	4AL		1.23	3.30	15.10	
FAGA075	90467	35.1	36.0	.9	.9	4L14		2.20	3.48	34.30	
FAGA075	90468	36.0	37.5	1.5	1.5	4L14		2.35	4.32	31.20	
FAGA075	90469	37.5	39.0	1.5	1.5	4L14		1.65	3.06	24.30	
FAGA075	90470	39.0	40.8	1.8	1.8	4A4		1.23	4.59	18.20	
FAGA075	90471	40.8	42.1	1.3	1.3	4A4		2.18	5.88	31.20	
FAGA075	90472	42.1	43.6	1.5	1.5	4AG		1.48	3.48	24.30	
FAGA075	90473	43.6	44.8	1.2	1.2	4A4		1.63	3.78	24.30	
FAGA075	90474	44.8	45.9	1.1	1.1	4A4		2.20	5.76	39.40	
FAGA075	90475	45.9	47.2	1.3	1.3	5D4a		.34	1.90	6.20	
FAGA075	90476	47.2	48.8	1.6	1.6	4AD		3.30	5.22	50.40	
FAGA075	90477	48.8	50.4	1.6	1.6	4CC		.28	.96	5.10	
FAGA075	90478	50.4	51.5	1.1	1.1	4DC		2.93	5.88	45.30	
FAGA075	90479	53.6	56.7	3.1	3.1	4AG		1.60	1.96	21.30	
FAGA075	90480	56.7	58.8	2.1	2.1	4AG		1.48	3.36	22.30	
FAGA075	90481	58.8	59.6	.8	.8	4A4		1.93	4.50	34.30	
FAGA075	90482	59.6	61.3	1.7	1.7	4A4		3.90	9.08	64.50	
FAGA075	90483	61.3	62.8	1.5	1.5	4A4		3.15	5.16	43.20	
FAGA075	90484	62.8	64.9	2.1	2.1	4A4		4.35	6.36	57.60	
FAGA075	90485	64.9	67.7	2.8	2.8	4A4		1.95	3.30	30.20	
FAGA075	90486	68.4	69.8	1.4	1.4	4L41		2.85	4.50	37.40	
FAGA075	90487	69.8	71.6	1.8	1.8	4AL		2.13	3.96	35.30	
FAGA075	90488	71.6	72.8	1.2	1.2	4L41		1.40	3.54	20.20	
FAGA075	90489	72.8	73.9	1.1	1.1	4L41		2.43	5.40	35.30	
FAGA075	90490	75.1	75.9	.8	.8	4L41		1.45	4.74	20.20	
FAGA075	90491	75.9	77.4	1.5	1.5	4L41		3.60	10.82	50.40	
FAGA075	90492	77.4	78.9	1.5	1.2	4L41		3.60	7.08	60.20	
FAGA075	90493	78.9	80.5	1.6	1.5	4L41		3.45	5.64	51.40	
FAGA075	90494	80.5	82.1	1.6	1.6	4A41		4.05	7.08	56.60	
FAGA075	90495	82.1	84.1	2.0	2.0	5D4a		.70	2.58	9.90	
FAGA075	90496	84.1	85.8	1.7	1.7	4A4		4.43	7.68	60.30	
FAGA075	90497	85.8	87.8	2.0	2.0	4A4		2.33	4.44	34.30	
FAGA075	90498	87.8	89.1	1.3	1.3	4L14		3.53	6.48	47.30	
FAGA075	90499	89.1	90.8	1.7	1.7	4L14		4.99	8.76	70.60	
FAGA075	90500	90.8	91.9	1.1	1.1	4L14		3.68	7.80	48.30	
FAGA075	90501	92.3	93.9	1.6	1.6	4A4		1.63	3.60	24.30	
FAGA075	90502	93.9	96.3	2.4	2.4	4AG		1.10	3.12	15.10	
FAGA075	90503	96.3	97.8	1.5	1.5	4A4		2.25	7.08	34.30	
FAGA075	90504	97.8	99.1	1.3	1.3	4DC		3.23	6.72	40.40	
FAGA075	90505	99.1	100.3	1.2	1.2	4L14		3.98	6.60	52.40	
FAGA075	90506	100.3	103.3	3.0	3.0	4A4		6.09	14.43	80.60	
FAGA075	90507	103.3	104.7	1.4	1.4	4A43		3.23	8.97	53.50	
FAGA075	90508	104.7	106.2	1.5	1.5	4A43		2.38	5.34	35.30	
FAGA075	90509	106.2	107.7	1.5	1.5	4A43		4.95	6.36	59.30	
FAGA075	90510	107.7	108.7	1.0	1.0	4A43		2.85	5.64	45.30	
FAGA075	90511	109.1	110.9	1.8	1.8	4A4		3.08	5.88	40.40	

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK UNIT	CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT
		FROM	TO								
FAGA075	90512	245.0	246.5	1.5	1.5	4E4		12.75	9.23	171.40	
FAGA075	90513	249.0	250.6	1.6	1.6	4K4		6.68	5.16	78.50	
FAGA075	90514	250.6	252.2	1.6	1.6	4AK		6.08	4.20	67.50	
FAGA075	90515	253.0	253.6	.6	.6	4AD		4.13	10.89	59.70	
FAGA075	90516	253.6	254.7	1.1	1.1	4G4		3.90	7.44	57.60	
FAGA075	90517	259.4	261.4	2.0	2.0	4G4		5.40	10.50	81.60	
FAGA075	90518	261.4	262.5	1.1	1.1	4AG		4.50	8.23	67.50	
FAGA075	90519	262.8	264.3	1.5	1.5	4G4		4.80	7.62	70.60	
FAGA075	90520	264.3	264.9	.6	.6	4G4		5.10	8.56	74.70	
FAGA008	90521	72.7	74.7	2.0	.0	4A0		.98	1.12	13.70	
FAGA008	90522	74.7	76.2	1.5	.0	4A0		.90	1.26	16.50	
FAGA008	90523	76.2	80.2	4.0	.0	4A0		.80	.90	11.00	
FAGA008	90524	80.2	81.4	1.2	.0	4A0		.21	.08	2.70	
FAGA008	90525	93.5	95.1	1.6	.0	4D5		2.03	4.08	37.00	
FAGA008	90526	95.1	95.3	.2	.0	4D5		2.03	4.08	37.00	
FAGA008	90527	95.3	96.9	1.6	.0	4D5		2.48	4.62	31.50	
FAGA008	90528	96.9	98.1	1.2	.0	4D5		3.08	6.48	39.80	
FAGA008	90529	177.9	180.6	2.7	.0	4D5		3.23	6.11	50.70	
FAGA012	90534	247.2	250.2	3.0	.0	4C5	.04	2.00	2.70	30.90	
FAGA012	90536	250.2	253.3	3.1	.0	4D5	.07	3.45	3.06	44.60	
FAGA012	90537	253.3	256.3	3.0	.0	4D5	.05	2.35	3.48	38.40	
FAGA020	90538	183.8	185.0	1.2	1.2	5D4*	.04	.43	.70	11.00	
FAGA020	90539	185.0	186.8	1.8	1.8	4A4	.10	2.48	4.14	41.80	
FAGA020	90540	188.1	189.6	1.5	1.5	4A0	.04	1.73	3.06	28.10	
FAGA020	90541	189.6	191.1	1.5	1.5	4A4	.08	3.38	2.46	43.20	
FAGA020	90542	191.1	192.6	1.5	1.5	4A4	.04	2.50	3.54	56.20	
FAGA020	90543	192.6	194.2	1.6	1.5	4A4	.06	2.85	5.52	35.70	
FAGA020	90544	202.5	204.8	2.3	2.3	4A4	.14	2.42	3.16	37.90	
FAGA020	90545	204.8	206.0	1.2	1.2	4A4	.04	5.25	8.04	78.20	
FAGA020	90546	215.5	217.3	1.8	1.8	4A4	.23	4.79	6.68	87.80	
FAGA020	90547	217.3	218.8	1.5	1.5	4A4	.04	3.38	7.44	66.50	
FAGA020	90548	218.8	220.4	1.6	1.5	4A4	.06	2.85	6.72	50.10	
FAGA020	90549	220.4	221.9	1.5	1.5	4A4	.05	3.15	7.44	55.50	
FAGA020	90550	221.9	223.4	1.5	1.5	4A4	.04	2.43	5.40	45.90	
FAGA020	90551	223.4	224.9	1.5	1.5	4A4	.06	2.00	3.72	37.70	
FAGA020	90552	224.9	226.5	1.6	1.5	4A0	.06	.58	1.18	19.20	
FAGA022	90553	154.2	154.7	.5	.5	4E80	.44	1.45	1.58	23.30	
FAGA022	90554	181.0	183.2	2.2	2.2	4E4	.13	5.03	5.52	68.60	
FAGA022	90555	183.2	184.8	1.6	1.5	4DL	.16	6.00	6.84	105.90	
FAGA022	90556	184.8	186.9	2.1	2.1	4L41	.13	.78	1.06	9.90	
FAGA022	90557	186.9	188.7	1.8	1.8	4H2S	.24	.85	2.40	30.20	
FAGA022	90558	229.9	231.0	1.1	1.1	4E4	.12	4.35	8.50	59.00	
FAGA022	90559	231.0	232.1	1.1	.7	4E4	.27	6.83	8.40	133.00	
FAGA022	90560	232.1	233.8	1.7	.9	4E4	.15	3.23	4.44	50.70	
FAGA022	90561	233.8	236.8	3.0	.3	4A4	.09	5.33	8.88	78.20	
FAGA022	90562	236.8	239.9	3.1	.3	4A4	.07	2.35	5.16	48.00	
FAGA022	90563	239.9	242.6	2.7	2.7	4A4	.06	2.08	4.56	59.00	
FAGA022	90564	242.6	243.4	.8	.2	4L12	.08	1.93	3.06	23.30	
FAGA022	90565	243.4	245.8	2.4	2.4	4L12	.08	.23	.43	5.50	
FAGA022	90566	245.8	247.0	1.2	1.2	4A0	.12	.63	.25	20.60	

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK UNIT	CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT
		FROM	TO								
FAGA022	90567	247.0	250.0	3.0	3.0	4A4	.10	3.83	6.96	52.10	
FAGA022	90568	250.0	251.3	1.3	1.3	4E0	.28	.69	1.40	16.50	
FAGA022	90569	251.3	252.6	1.3	1.2	4E0	.31	2.08	2.00	45.30	
FAGA022	90570	252.6	254.5	1.9	1.9	4A4	.12	4.35	8.16	62.40	
FAGA022	90571	254.5	257.4	2.9	2.9	4E4	.21	4.35	7.68	66.50	
FAGA022	90572	270.0	270.5	.5	.5	4G4	.08	6.68	11.45	152.20	
FAGA022	90573	274.4	275.3	.9	.9	4AC	.04	1.58	3.00	27.40	
FAGA022	90574	275.3	276.8	1.5	1.5	4D4	.08	6.60	12.67	94.60	
FAGA022	90575	276.8	278.8	2.0	2.0	4D4	.15	6.00	11.92	127.50	
FAGA022	90576	342.9	344.9	2.0	2.0	4EG4	.10	4.35	7.20	80.90	
FAGA022	90577	344.9	345.4	.5	.3	4E4	.09	6.08	10.65	98.70	
FAGA022	90578	345.4	347.5	2.1	1.8	4A43	.04	3.53	6.36	43.90	
FAGA022	90579	347.5	349.2	1.7	1.6	4A43	.04	3.53	6.60	49.40	
FAGA022	90580	349.2	352.2	3.0	.3	4G4	.10	4.88	7.80	100.10	
FAGA022	90581	352.2	354.8	2.6	2.6	4G4		5.18	8.76	88.80	
FAGA022	90582	354.8	355.5	.7	.6	5C4*		.50	.77	6.20	
FAGA022	90583	355.5	356.3	.8	.8	4G4		4.58	7.80	87.80	
FAGA022	90584	356.3	356.7	.4	.3	4G0		2.55	3.54	33.30	
FAGA022	90585	361.1	362.3	1.2	1.2	4GL		3.08	5.28	64.50	
FAGA022	90586	362.3	363.3	1.0	.7	5B62		.14	.12	1.00	
FAGU036	90587	15.2	16.8	1.6	1.6	4J0		8.17	10.82	133.00	
FAGU037	90588	10.1	10.7	.6	.6	4E4		2.15	5.07	32.20	
FAGU037	90589	10.7	12.2	1.5	1.5	4E4		2.10	4.98	49.40	
FAGU037	90590	12.2	13.7	1.5	1.5	4EAG		2.60	5.68	47.30	
FAGU037	90591	13.7	15.2	1.5	.6	4EG4		4.70	13.68	97.70	
FAGU037	90592	15.2	16.8	1.6	.4	4E4		4.93	12.76	80.60	
FAGU037	90593	16.8	18.3	1.5	1.2	4E4		4.80	10.26	86.70	
FAGU037	90594	18.3	19.8	1.5	1.0	4E4		6.51	13.37	98.70	
FAGU037	90595	19.8	21.3	1.5	1.5	4E4		6.36	13.12	99.80	
FAGU037	90596	21.3	22.9	1.6	1.4	4E4		4.65	6.77	80.60	
FAGU037	90597	22.9	24.4	1.5	1.5	4A31		1.43	1.68	24.30	
FAGU037	90598	24.4	25.9	1.5	1.4	4A31		1.18	1.75	24.30	
FAGA111	90599	271.9	273.9	2.0	2.0	4CA0		.80	1.46	19.20	
FAGA111	90600	273.9	275.4	1.5	1.5	4CA0		.85	1.14	8.90	
FAGA111	90601	275.4	276.2	.8	.8	4CA0		1.03	1.72	12.00	
FAGA111	90602	277.8	279.8	2.0	2.0	4CA0		1.00	1.10	15.10	
FAGA111	90603	279.8	281.0	1.2	1.2	4AC0		.78	.96	14.10	
FAGA111	90604	281.0	282.1	1.1	1.1	4AC0		.88	1.12	13.00	
FAGA131	90605	115.2	117.0	1.8	.3	4A4		2.95	4.60	33.30	
FAGA131	90606	117.0	118.9	1.9	.9	4A4		4.50	8.70	75.80	
FAGU185	90607	6.1	7.6	1.5	1.3	4AG		1.23	1.85	20.20	
FAGU185	90608	7.6	9.1	1.5	1.3	4A34		6.43	14.02	93.90	
FAGU185	90609	9.1	10.7	1.6	1.6	4A34		6.83	15.27	110.10	
FAGU185	90610	10.7	12.2	1.5	1.5	4DE4		5.86	11.84	66.50	
FAGU185	90611	12.2	13.7	1.5	1.5	4E4		7.81	15.99	84.70	
FAGU185	90612	13.7	15.2	1.5	1.5	4E4		6.43	11.59	84.70	
FAGU185	90613	15.2	16.8	1.6	1.6	4E4		8.11	17.43	104.90	
FAGU185	90614	16.8	18.3	1.5	1.5	4D4		10.47	26.45	172.50	
FAGU185	90615	18.3	19.8	1.5	1.5	4D34		6.23	17.52	90.90	
FAGU185	90616	19.8	20.5	.7	.7	4D34		9.69	20.65	141.30	

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK UNIT	CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT
		FROM	TO								
FAGU185	90617	57.9	58.6	.7	.7	4E46		5.50	9.70	80.60	
FAGU191	90618	6.1	9.1	3.0	2.3	4A13		.45	.80	9.90	
FAGU191	90619	9.1	12.2	3.1	3.0	4A13		.60	1.30	25.40	
FAGU191	90620	12.2	13.7	1.5	1.4	4A13		3.35	3.75	50.40	
FAGU191	90621	13.7	15.2	1.5	1.5	4DE4		7.15	12.83	94.60	
FAGU191	90622	15.2	16.8	1.6	1.6	4EA		5.00	9.60	83.70	
FAGU191	90623	16.8	18.3	1.5	1.4	4E4		6.62	12.28	86.70	
FAGU191	90624	18.3	19.8	1.5	1.1	4ED4		6.85	13.69	103.90	
FAGU191	90625	19.8	21.3	1.5	1.1	4D45		8.96	14.71	126.20	
FAGU191	90626	21.3	24.3	3.0	1.7	4DE4		6.95	12.53	109.00	
FAGU191	90627	50.3	53.3	3.0	1.2	4E4		5.33	15.46	75.80	
FAGU191	90628	53.3	56.4	3.1	1.1	4EC		4.40	13.20	67.50	
FAGU191	90629	56.4	57.9	1.5	.9	4E4		7.05	16.45	114.20	
FAGU193	90630	36.5	38.1	1.6	1.6	4EG4		7.55	10.60	100.80	
FAGU193	90631	38.1	39.6	1.5	1.5	4G4		4.10	9.75	50.40	
FAGU193	90632	39.6	41.1	1.5	1.4	4GA4		6.55	10.21	78.90	
FAGU193	90633	41.1	42.7	1.6	1.6	4A4		6.25	9.20	98.70	
FAGU195	90634	16.8	18.3	1.5	1.2	4E4		3.95	10.08	57.60	
FAGU195	90635	18.3	19.8	1.5	1.4	4E4		4.33	11.32	59.30	
FAGU195	90636	19.8	21.3	1.5	1.4	4E4		5.80	12.98	91.90	
FAGU195	90637	21.3	22.9	1.6	1.5	4E4		6.92	15.01	108.00	
FAGU195	90638	22.9	24.4	1.5	1.5	4E4		3.40	7.80	50.40	
FAGU195	90639	24.4	25.9	1.5	1.3	4D4		7.67	14.91	114.90	
FAGU195	90640	25.9	27.4	1.5	1.5	4E4		7.94	17.86	114.90	
FAGU195	90641	27.4	29.0	1.6	1.0	4E4		6.95	14.29	96.70	
FAGU195	90642	29.0	30.5	1.5	1.2	4A13		6.15	7.99	84.70	
FAGU195	90643	30.5	33.5	3.0	1.0	4A13		.05	.13	6.17	
FAGU196	90644	.0	3.0	3.0	1.6	4AG		1.80	1.70	20.20	
FAGU196	90645	3.0	4.5	1.5	1.4	4AG		1.95	2.93	26.40	
FAGU196	90646	4.5	6.0	1.5	1.3	4AG		1.63	1.63	22.30	
FAGU196	90647	6.0	7.5	1.5	1.5	4C0		1.60	.88	22.30	
FAGU196	90648	7.5	9.0	1.5	1.4	4C0		.88	.35	12.00	
FAGU196	90649	9.0	10.5	1.5	1.3	4AG		2.20	2.00	32.20	
FAGU196	90650	10.5	12.0	1.5	1.3	4A4		2.88	2.55	36.30	
FAGU196	90651	12.0	13.5	1.5	1.3	4A4		2.70	2.95	32.20	
FAGU196	90652	13.5	15.0	1.5	1.2	4AG		2.80	1.25	30.20	
FAGU196	90653	15.0	16.5	1.5	1.5	4AG		3.10	1.85	31.20	
FAGU196	90654	16.5	18.0	1.5	1.3	4AG		2.70	.80	26.40	
FAGU196	90655	18.0	19.5	1.5	1.5	4AG		.13	.55	3.10	
FAGU196	90656	19.5	21.0	1.5	1.5	4AG		.10	.10	6.20	
FAGU196	90657	21.0	22.5	1.5	1.5	4AG		.14	.35	6.20	
FAGU196	90658	22.5	25.5	3.0	2.7	4AG		.75	.73	8.90	
FAGU196	90659	25.5	28.5	3.0	2.8	4AG		.18	.40	3.10	
FAGU196	90660	28.5	31.5	3.0	2.8	4A0		.13	.93	3.10	
FAGU196	90661	31.5	34.5	3.0	3.0	4AG		.53	1.23	8.90	
FAGU196	90662	34.5	36.6	2.1	2.0	4A4		1.95	3.40	30.20	
FAGU196	90663	36.6	38.1	1.5	1.5	4AE		2.58	4.15	41.50	
FAGU196	90664	38.1	39.6	1.5	1.5	4E4		6.23	8.77	92.90	
FAGU196	90665	39.6	40.3	.7	.7	4E4		6.10	8.47	102.90	
FAGU196	90666	62.5	64.0	1.5	1.5	4EG		5.00	8.21	93.90	

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK UNIT	CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT
		FROM	TO								
FAGU196	90667	64.0	65.5	1.5	1.5	4EG		6.85	5.10	184.50	
FAGU196	90668	65.5	67.0	1.5	1.5	4G4		5.70	8.06	108.00	
FAGU196	90669	67.0	68.5	1.5	1.5	4EG		4.00	6.80	69.60	
FAGU196	90670	68.5	70.0	1.5	1.5	4EG4		5.00	8.49	82.60	
FAGU196	90671	70.0	71.5	1.5	1.5	4EG4		4.35	7.50	76.80	
FAGU196	90672	94.5	96.0	1.5	.5	4J4		4.28	19.19	61.40	
FAGU196	90673	96.0	97.5	1.5	1.2	4J4		9.02	20.34	150.20	
FAGU196	90674	97.5	99.0	1.5	1.3	3GG		2.53	5.65	42.50	
FAGU196	90675	99.0	100.5	1.5	1.3	4E4		2.03	4.55	36.30	
FAGU196	90676	100.5	102.0	1.5	1.3	4E4		4.65	8.31	70.60	
FAGU196	90677	102.0	103.5	1.5	1.2	4E10		1.05	3.68	25.40	
FAGU196	90678	103.5	105.0	1.5	1.4	4E4		2.23	3.15	39.40	
FAGU196	90679	105.0	106.5	1.5	1.3	4E4		1.63	4.03	30.20	
FAGU196	90680	106.5	108.0	1.5	1.1	4C0		1.20	3.18	25.40	
FAGU196	90681	108.0	109.5	1.5	.9	4D0		2.58	2.75	45.30	
FAGU196	90682	109.5	111.0	1.5	.5	4D0		3.25	4.85	48.30	
FAGU189	90683	56.4	58.4	2.0	1.8	4E4		2.65	5.40	32.20	
FAGU189	90684	58.4	60.4	2.0	1.3	4A10		1.18	3.40	21.30	
FAGU189	90685	60.4	61.0	.6	.6	4E0		1.05	1.80	25.40	
FAGU189	90686	61.0	62.5	1.5	1.5	5D4\$		.18	1.10	3.10	
FAGU189	90687	82.9	85.3	2.4	2.4	4E0		3.20	1.80	29.10	
FAGU189	90688	85.3	87.5	2.2	2.0	4E0		1.08	.85	16.10	
FAGU189	90689	87.5	88.4	.9	.8	4E0		.55	.90	14.10	
FAGU189	90690	88.4	89.9	1.5	1.5	4E0		1.03	1.43	18.20	
FAGU189	90691	89.9	90.8	.9	.7	4E0		1.25	1.23	17.10	
FAGU189	90692	90.8	93.0	2.2	1.9	4E0		1.85	2.15	27.40	
FAGU189	90693	93.0	93.9	.9	.2	4C0		1.05	1.43	12.00	
FAGU189	90694	93.9	95.4	1.5	1.5	4C0		.40	.38	8.20	
FAGU189	90695	95.4	96.3	.9	.5	4C0		.53	.85	5.10	
FAGU189	90696	96.3	97.8	1.5	1.5	4C0		.55	.98	6.20	
FAGU189	90697	97.8	100.3	2.5	1.6	4C0		2.78	2.13	24.30	
FAGU189	90698	100.3	101.8	1.5	1.4	4D0		3.68	2.03	32.20	
FAGU189	90699	101.8	103.6	1.8	1.7	4C0		1.85	1.20	20.20	
FAGU189	90700	103.6	105.2	1.6	1.6	4D0		2.48	2.63	29.10	
FAGU189	90701	105.2	106.7	1.5	1.5	4D0		4.45	4.95	67.50	
FAGU189	90702	106.7	108.2	1.5	1.5	4C0		1.53	1.13	25.40	
FAGU189	90703	108.2	109.7	1.5	1.5	4E0		1.03	.83	15.10	
FAGU189	90704	112.8	114.3	1.5	1.5	4C0		2.03	2.65	36.30	
FAGU198	90705	45.7	47.2	1.5	1.5	4BE		2.20	1.15	39.40	
FAGU198	90706	47.2	49.0	1.8	1.8	4E0		2.88	1.85	42.50	
FAGU198	90707	90.5	92.0	1.5	1.5	4E46		5.76	8.04	101.80	
FAGU198	90708	92.0	93.5	1.5	1.5	4E46		6.65	9.70	123.10	
FAGU198	90709	93.5	94.7	1.2	1.2	4E46		5.44	9.70	91.90	
FAGU198	90710	134.1	135.6	1.5	1.5	4EA4		2.88	2.85	36.30	
FAGU198	90711	135.6	137.1	1.5	1.5	4A1		.88	.88	13.00	
FAGU198	90712	137.1	138.6	1.5	1.5	4A1		.08	.10	4.10	
FAGU198	90713	146.9	148.4	1.5	1.5	4A1		1.28	1.50	20.20	
FAGU198	90714	148.4	149.9	1.5	1.3	4A1		.18	.70	7.20	
FAGU198	90715	149.9	151.4	1.5	1.5	4A1		1.18	1.33	23.30	
FAGU199	90716	2.1	3.6	1.5	.9	4E4		8.39	12.65	124.10	

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK UNIT	CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT
		FROM	TO								
FAGU199	90717	3.6	5.1	1.5	1.3	4EG4		7.40	10.21	114.20	
FAGU199	90718	5.1	6.6	1.5	1.4	4G4		6.40	8.85	92.90	
FAGU199	90719	6.6	8.1	1.5	1.5	4G4		7.85	10.31	113.10	
FAGU199	90720	8.1	9.6	1.5	1.2	4G4		6.50	8.95	75.80	
FAGU199	90721	9.6	11.1	1.5	1.0	4G4		6.75	10.15	76.80	
FAGU199	90722	11.1	12.6	1.5	1.0	4E4		6.97	8.69	104.90	
FAGU199	90723	12.6	14.1	1.5	1.0	5C4*		3.60	8.16	46.30	
FAGU199	90724	14.1	15.6	1.5	.8	4A10		3.03	3.35	47.30	
FAGU199	90725	15.6	17.1	1.5	1.3	4AE4		6.75	6.52	97.70	
FAGU199	90726	17.1	18.6	1.5	1.4	4G4		8.60	11.52	156.30	
FAGU199	90727	18.6	20.1	1.5	1.2	4G4		7.40	9.93	114.20	
FAGU199	90728	20.1	21.6	1.5	1.4	4G4		7.00	9.70	93.90	
FAGU199	90729	21.6	23.1	1.5	.9	4G4		7.20	9.65	101.80	
FAGU199	90730	23.1	24.6	1.5	.8	4G4		4.18	6.31	79.50	
FAGU199	90731	27.0	28.5	1.5	1.5	4G4		6.10	10.21	108.00	
FAGU199	90732	28.5	30.0	1.5	1.4	4G4		5.40	9.55	98.70	
FAGU199	90733	30.0	31.5	1.5	1.5	4G4		6.20	9.85	139.20	
FAGU199	90734	31.5	33.0	1.5	1.5	4G4		6.40	9.25	104.90	
FAGU199	90735	33.0	34.5	1.5	1.3	4G4		5.10	9.78	85.70	
FAGU199	90736	34.5	36.0	1.5	1.1	4EG4		4.55	9.18	62.40	
FAGU199	90737	103.0	104.5	1.5	1.4	4E4		3.90	3.65	49.40	
FAGU199	90738	104.5	106.0	1.5	1.5	4E0		1.83	1.05	29.10	
FAGU199	90739	106.0	107.5	1.5	1.1	4K0		1.13	.30	27.40	
FAGU199	90740	107.5	109.0	1.5	1.5	4E4		6.80	6.47	68.60	
FAGU199	90741	109.0	110.5	1.5	1.3	4E0		1.95	1.73	23.30	
FAGU200	90742	6.0	7.9	1.9	1.2	4E4		7.95	15.80	126.20	
FAGU200	90743	7.9	9.4	1.5	1.1	4E4		9.17	16.40	138.20	
FAGU200	90744	9.4	10.9	1.5	.9	4E4		8.88	14.23	122.10	
FAGU200	90745	10.9	12.4	1.5	1.3	4E4		9.94	11.45	147.10	
FAGU200	90746	12.4	13.9	1.5	.9	4E4		6.30	10.43	100.80	
FAGU200	90747	13.9	15.4	1.5	.9	5A6		.88	2.38	16.10	
FAGU200	90748	15.4	16.9	1.5	1.1	4E4		6.63	11.55	110.10	
FAGU200	90749	16.9	18.4	1.5	1.0	4E4		9.52	15.70	162.50	
FAGU200	90750	18.4	20.0	1.6	1.0	4E4		8.63	14.68	117.30	
FAGU200	90751	21.3	22.9	1.6	1.5	4A0		2.33	1.10	31.20	
FAGU200	90752	22.9	24.4	1.5	1.5	4A4		2.50	4.30	43.50	
FAGU200	90753	24.4	27.0	2.6	1.4	4A4		2.05	3.45	30.20	
FAGU204	90754	19.8	21.3	1.5	1.3	4E4		7.32	12.90	102.90	
FAGU204	90755	21.3	22.9	1.6	1.2	4E4		6.48	13.51	89.80	
FAGU204	90756	22.9	24.4	1.5	1.5	4EK4		2.33	8.26	59.30	
FAGU204	90757	24.4	25.9	1.5	.9	4E4		3.45	9.60	49.00	
FAGU204	90758	25.9	27.4	1.5	1.4	4E4		5.51	9.37	72.70	
FAGU204	90759	27.4	29.0	1.6	1.4	4E4		11.45	17.33	150.20	
FAGU204	90760	29.0	30.7	1.7	1.6	4E4		7.25	10.67	114.20	
FAGU204	90761	30.7	32.2	1.5	1.3	4A1		1.60	2.90	26.40	
FAGU207	90762	.0	4.6	4.6	1.5	4A43		4.80	8.78	82.60	
FAGU207	90763	4.6	6.1	1.5	1.4	4A43		4.10	7.87	63.40	
FAGU207	90764	7.6	9.1	1.5	1.2	4A43		3.00	6.67	59.30	
FAGU207	90765	9.1	10.6	1.5	1.5	4A43		2.15	4.00	38.40	
FAGU207	90766	10.6	12.1	1.5	1.5	4A43		3.10	4.56	54.50	

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK UNIT	CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT
		FROM	TO								
FAGU207	90767	12.1	13.6	1.5	1.5	4A43		2.95	5.56	52.50	
FAGU207	90768	13.6	15.1	1.5	1.2	4A43		3.00	5.00	45.30	
FAGU207	90769	15.1	16.7	1.6	1.0	4A43		2.90	7.98	43.50	
FAGU207	90770	16.7	18.2	1.5	1.0	4A43		2.68	3.90	35.30	
FAGU207	90771	18.2	20.4	2.2	2.1	4A43		3.90	8.48	59.30	
FAGU215	90772	4.2	6.0	1.8	.7	4A34		2.95	6.14	53.50	
FAGU215	90773	7.8	9.3	1.5	1.4	4AL		1.28	2.10	23.30	
FAGU215	90774	9.3	10.8	1.5	1.5	4AC		1.58	2.33	25.40	
FAGU215	90775	10.8	12.0	1.2	1.2	4ACL		1.33	2.70	25.40	
FAGU215	90776	65.5	67.1	1.6	1.0	4G4		5.99	9.17	84.70	
FAGU215	90777	67.1	68.6	1.5	1.2	4A4		5.10	9.25	86.70	
FAGU215	90778	68.6	70.1	1.5	1.2	4AL		3.63	6.14	59.30	
FAGU215	90779	100.6	103.6	3.0	3.0	4A1		.05	.18	2.10	
FAGU215	90780	103.6	106.7	3.1	2.6	4A1		.05	.38	3.10	
FAGU215	90781	117.3	118.8	1.5	1.5	4A4		2.23	4.00	38.40	
FAGU215	90782	118.8	120.4	1.6	1.5	4A0		1.55	2.93	20.20	
FAGU215	90783	129.5	131.1	1.6	.2	4E4		5.96	4.07	71.70	
FAGU215	90784	131.1	132.6	1.5	.2	4L0		2.43	2.60	32.20	
FAGU216	90785	.0	1.5	1.5	.4	4A34		3.88	5.57	65.50	
FAGU216	90786	1.5	3.0	1.5	1.5	4A34		1.90	4.30	37.40	
FAGU216	90787	3.0	4.6	1.6	1.6	4A34		2.93	6.17	56.60	
FAGU216	90788	4.6	6.1	1.5	1.5	4A34		3.95	7.21	70.60	
FAGU216	90789	6.1	7.6	1.5	1.5	4A34		5.00	10.06	80.60	
FAGU216	90790	7.6	9.1	1.5	1.5	4A34		2.58	5.46	41.50	
FAGU216	90791	9.1	10.7	1.6	1.6	4A34		2.75	6.70	45.30	
FAGU216	90792	10.7	12.5	1.8	1.7	4A34		1.48	4.38	26.40	
FAGU216	90793	35.1	36.6	1.5	1.5	4E4		9.57	19.93	138.20	
FAGU216	90794	36.6	38.1	1.5	1.5	4E4		13.40	21.48	215.70	
FAGU216	90795	38.1	39.6	1.5	1.5	4E4		10.43	18.62	191.70	
FAGU216	90796	46.1	48.1	2.0	2.0	4D4		5.55	9.52	96.70	
FAGU216	90797	49.8	51.8	2.0	2.0	4D0		3.78	3.75	50.40	
FAGU216	90798	51.8	53.3	1.5	1.5	4A3		1.05	1.35	17.10	
FAGU192	90799	.0	1.9	1.9	1.1	4A4		2.13	4.10	27.40	
FAGU192	90800	1.9	3.8	1.9	1.7	4A4		2.93	2.70	35.30	
FAGU192	90801	3.8	5.3	1.5	1.4	4C0		.85	1.18	9.90	
FAGU192	90802	5.3	6.8	1.5	1.5	4C0		1.93	2.50	22.30	
FAGU192	90803	6.8	8.3	1.5	1.5	4C0		1.10	1.05	13.00	
FAGU192	90804	8.3	9.8	1.5	1.5	4C0		.95	1.43	9.90	
FAGU192	90805	9.8	12.8	3.0	3.0	4C0		1.03	1.48	13.00	
FAGU192	90806	15.0	16.5	1.5	1.4	4D0		2.48	3.25	35.30	
FAGU192	90807	16.5	18.0	1.5	1.5	4C0		1.93	2.80	22.30	
FAGU192	90808	18.0	19.5	1.5	1.5	4C0		1.50	2.00	17.10	
FAGU192	90809	19.5	21.0	1.5	.0	4C0		2.05	2.93	24.30	
FAGU192	90810	21.0	22.5	1.5	1.5	4C0		2.08	2.85	25.40	
FAGU192	90811	60.7	63.7	3.0	2.8	4A0		.35	.83	8.90	
FAGU192	90812	63.7	66.7	3.0	2.6	4A0		1.38	2.20	22.30	
FAGU192	90813	66.7	69.0	2.3	2.0	4A0		.03	.43	7.20	
FAGU192	90814	69.0	70.5	1.5	1.5	4E4		3.93	5.25	65.50	
FAGU192	90815	70.5	72.0	1.5	1.5	4EG4		3.18	7.78	57.60	
FAGU192	90816	72.0	73.5	1.5	1.5	4E46		4.50	8.24	65.50	

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK UNIT	CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT
		FROM	TO								
FAGU192	90817	73.5	75.0	1.5	1.5	4E46		2.63	4.60	33.30	
FAGU192	90818	75.0	76.5	1.5	1.5	4E60		1.13	3.18	17.10	
FAGU192	90819	76.5	78.0	1.5	1.5	4EG0		1.10	2.93	12.00	
FAGU192	90820	78.0	79.5	1.5	1.5	4EG		3.23	6.01	50.40	
FAGU192	90821	79.5	81.0	1.5	1.5	4EG4		5.85	11.16	85.70	
FAGU192	90822	81.0	82.5	1.5	1.5	4E4		4.65	3.35	50.40	
FAGU192	90823	82.5	84.0	1.5	1.5	4E0		2.20	1.75	29.10	
FAGU192	90824	84.0	85.5	1.5	1.5	4E4		3.28	4.40	51.40	
FAGU192	90825	85.5	87.0	1.5	1.2	4E4		4.08	6.25	62.40	
FAGU192	90826	87.0	88.5	1.5	1.3	4L4		1.05	2.13	15.10	
FAGU192	90827	88.5	90.0	1.5	1.5	4E46		4.78	7.17	62.40	
FAGU192	90828	90.0	91.5	1.5	1.4	4E46		3.90	7.88	60.30	
FAGU192	90829	91.5	93.0	1.5	1.3	4A0		.88	1.30	16.10	
FAGU192	90830	93.0	94.5	1.5	1.5	4E4		4.05	7.73	60.30	
FAGU192	90831	94.5	96.0	1.5	1.5	4A4		3.00	4.60	44.20	
FAGU192	90832	96.0	97.5	1.5	1.5	4EA4		2.75	5.56	40.50	
FAGU192	90833	97.5	99.0	1.5	1.5	4A0		.93	1.43	29.10	
FAGU192	90834	99.0	100.5	1.5	1.5	4AG		3.00	6.54	51.40	
FAGU192	90835	100.5	102.0	1.5	1.5	4A34		4.03	7.42	62.40	
FAGU192	90836	102.0	103.5	1.5	1.5	4A4		2.05	3.68	32.20	
FAGU192	90837	103.5	105.0	1.5	1.5	4A4		4.70	4.70	61.40	
FAGU192	90838	105.0	106.5	1.5	1.5	4A31		.45	.33	16.10	
FAGU192	90839	106.5	108.0	1.5	1.5	4AC3		.08	1.38	8.20	
FAGU192	90840	108.0	109.5	1.5	1.5	4A1		.13	1.15	11.00	
FAGU192	90841	109.5	111.0	1.5	1.5	4A1		.10	.30	9.90	
FAGU192	90842	111.0	112.5	1.5	1.5	4A1		.08	.25	13.00	
FAGU192	90843	112.5	114.0	1.5	1.5	4A1		.08	.53	12.00	
FAGU192	90844	114.0	115.5	1.5	1.5	4C30		.15	1.03	12.00	
FAGU192	90845	115.5	117.3	1.8	1.5	4C30		.43	1.30	16.10	
FAGU194	90846	1.2	4.0	2.8	2.3	4A4		2.35	3.00	28.50	
FAGU194	90847	4.0	5.5	1.5	1.5	4C0		1.55	.93	19.20	
FAGU194	90848	5.5	7.0	1.5	1.4	4C0		1.03	1.40	11.00	
FAGU194	90849	7.0	8.5	1.5	1.5	4D0		1.98	3.10	27.40	
FAGU194	90850	8.5	10.0	1.5	1.5	4C0		.90	1.80	9.90	
FAGU194	90851	10.0	11.5	1.5	1.4	4C0		1.28	1.60	12.00	
FAGU194	90852	11.5	13.0	1.5	1.5	4C0		.93	1.30	8.90	
FAGU194	90853	13.0	14.5	1.5	1.3	4C0		.95	.63	11.00	
FAGU194	90854	14.5	17.5	3.0	2.7	4A0		2.33	2.55	33.30	
FAGU194	90855	17.5	19.8	2.3	2.3	4AC		2.05	2.75	28.50	
FAGU194	90856	39.5	41.0	1.5	1.5	4AC		.40	1.00	8.20	
FAGU194	90857	41.0	42.5	1.5	1.4	4AC		1.08	2.28	20.20	
FAGU194	90858	42.5	44.0	1.5	1.4	4AC		.53	1.13	12.00	
FAGU194	90859	44.0	45.5	1.5	1.5	4A0		.23	.78	6.20	
FAGU194	90860	45.5	47.0	1.5	1.5	4AC0		.23	.73	7.20	
FAGU194	90861	47.0	48.5	1.5	1.5	4A0		.13	.43	7.20	
FAGU194	90862	48.5	50.0	1.5	1.3	4A13		1.90	3.90	34.30	
FAGU194	90863	50.0	51.5	1.5	1.5	4A13		3.65	7.20	68.60	
FAGU194	90864	51.5	53.4	1.9	1.7	4EC		3.23	5.82	59.30	
FAGU194	90865	57.2	58.7	1.5	1.4	4CS3		3.00	4.25	58.60	
FAGU194	90866	58.7	60.2	1.5	1.5	4E4		8.97	11.07	114.90	

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK UNIT	CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT
		FROM	TO								
FAGU194	90867	60.2	61.7	1.5	1.3	4G4		4.23	7.93	96.70	
FAGU194	90868	61.7	63.2	1.5	1.4	4Q*		3.28	5.48	58.60	
FAGU194	90869	63.2	64.7	1.5	1.5	4EG		3.38	5.71	48.30	
FAGU194	90870	64.7	66.2	1.5	1.5	4E4		4.90	6.57	81.60	
FAGU194	90871	66.2	67.7	1.5	1.4	4EG		3.20	6.90	80.60	
FAGU194	90872	67.7	69.2	1.5	1.4	4E4		4.13	9.21	74.70	
FAGU194	90873	69.2	70.7	1.5	1.3	4E4		5.00	8.26	84.70	
FAGU194	90874	70.7	72.2	1.5	1.5	4E4		3.93	4.00	57.60	
FAGU194	90875	72.2	73.7	1.5	1.2	4EG		2.70	1.50	43.50	
FAGU194	90876	73.7	75.2	1.5	1.5	4E4		4.94	5.91	78.90	
FAGU194	90877	75.2	76.2	1.0	1.0	4E4		3.90	5.05	78.90	
FAGU194	90878	87.2	88.7	1.5	1.5	4A4		9.71	18.19	147.10	
FAGU194	90879	88.7	90.2	1.5	1.5	4E14		6.99	14.00	104.90	
FAGU194	90880	90.2	91.7	1.5	1.5	4E14		5.23	8.04	79.50	
FAGU194	90881	91.7	93.2	1.5	1.5	4EC		2.73	5.05	43.50	
FAGU194	90882	93.2	94.7	1.5	1.5	4C3		.55	1.05	15.10	
FAGU194	90883	94.7	96.2	1.5	1.5	4C3		.88	1.93	17.10	
FAGU194	90884	96.2	97.7	1.5	1.5	4D3		4.25	6.19	63.40	
FAGU194	90885	97.7	99.2	1.5	1.5	4C3		1.00	2.48	21.30	
FAGU194	90886	99.2	100.7	1.5	1.5	4C3		1.43	2.98	26.40	
FAGU194	90887	100.7	102.2	1.5	1.5	4C35		1.05	1.28	25.40	
FAGU194	90888	102.2	103.7	1.5	1.5	4C35		.13	.65	18.20	
FAGU194	90889	103.7	105.2	1.5	1.5	4C3		.48	.50	18.20	
FAGU194	90890	105.2	106.7	1.5	1.5	4D3		2.28	2.80	37.40	
FAGU194	90891	106.7	108.2	1.5	1.5	4D3		3.88	5.00	60.30	
FAGU194	90892	108.2	109.7	1.5	1.5	4C3		.70	1.63	25.40	
FAGU194	90893	109.7	111.4	1.7	1.5	4C3		2.08	1.93	34.30	
FAGU206	90894	1.5	3.0	1.5	1.4	4A4		4.35	8.98	66.50	
FAGU206	90895	3.0	4.6	1.6	1.4	4A34		3.45	4.60	45.30	
FAGU206	90896	4.6	6.1	1.5	1.5	4A34		5.70	4.00	67.50	
FAGU206	90897	6.1	7.6	1.5	1.3	4D54		9.75	6.33	114.20	
FAGU206	90898	7.6	9.1	1.5	1.4	4D5		4.78	4.25	58.60	
FAGU206	90899	9.1	12.2	3.1	3.1	4D5		3.65	4.20	43.50	
FAGU206	90900	12.2	13.7	1.5	1.5	4A43		6.50	2.50	69.60	
FAGU206	90901	13.7	15.2	1.5	1.5	4A43		8.50	4.40	89.80	
FAGU206	90902	15.2	16.8	1.6	1.5	4A43		4.03	2.03	46.30	
FAGU206	90903	16.8	18.3	1.5	1.5	4A43		5.04	2.33	55.50	
FAGU206	90904	18.3	19.8	1.5	1.5	4A43		4.85	1.63	55.50	
FAGU206	90905	19.8	21.3	1.5	1.5	4A43		5.70	1.48	64.50	
FAGU206	90906	21.3	22.9	1.6	1.6	4A34		8.55	7.52	83.70	
FAGU206	90907	22.9	24.4	1.5	1.5	4A34		3.70	2.70	41.50	
FAGU206	90908	24.4	25.9	1.5	1.5	4A34		3.33	4.10	47.30	
FAGU206	90909	25.9	27.4	1.5	1.2	4D0		2.15	4.66	37.40	
FAGU206	90910	27.4	29.0	1.6	1.5	4D0		2.38	5.00	44.20	
FAGU206	90911	29.0	30.5	1.5	1.4	4A4		2.15	4.76	40.50	
FAGU206	90912	30.5	32.0	1.5	1.5	4A4		1.90	3.95	39.40	
FAGU206	90913	32.0	33.5	1.5	1.5	4A4		1.60	3.73	33.30	
FAGU206	90914	33.5	35.1	1.6	1.6	4A4		1.90	4.68	39.40	
FAGU206	90915	35.1	36.6	1.5	1.5	4A0		1.75	2.53	31.20	
FAGU206	90916	36.6	38.1	1.5	1.5	4A4		3.35	6.48	57.60	

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK UNIT	CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT
		FROM	TO								
FAGU206	90917	38.1	39.6	1.5	1.5	4A4		2.48	4.06	46.30	
FAGU206	90918	39.6	41.1	1.5	1.5	4A4		3.30	7.44	66.50	
FAGU206	90919	41.1	42.7	1.6	1.5	4D5		1.80	3.30	29.10	
FAGU206	90920	42.7	44.2	1.5	1.5	4C5		1.15	1.40	15.10	
FAGU206	90921	44.2	45.7	1.5	1.5	4C5		1.40	2.88	23.30	
FAGU206	90922	45.7	47.2	1.5	1.5	4AC		1.38	3.25	26.40	
FAGU206	90923	47.2	48.8	1.6	1.6	4A4		1.68	4.18	30.20	
FAGU206	90924	48.8	50.3	1.5	1.4	4AG		1.43	3.18	21.30	
FAGU206	90925	50.3	51.8	1.5	1.5	4AG		1.50	3.00	24.30	
FAGU206	90926	51.8	53.3	1.5	.8	4A4		1.58	4.20	27.40	
FAGU206	90927	53.3	54.9	1.6	.8	4AC		1.70	2.48	26.40	
FAGU206	90928	54.9	56.4	1.5	.5	4E0		.63	1.30	11.00	
FAGU139	90929	42.7	44.2	1.5	1.5	4EL#		5.97	5.15		82.63
FAGU206	90930	57.9	59.4	1.5	.8	4A10		1.83	2.40	24.30	
FAGU206	90931	59.4	61.0	1.6	1.6	4CD5		2.20	5.50	30.20	
FAGU206	90932	61.0	62.5	1.5	.5	4AC		1.35	2.88	21.30	
FAGU206	90933	62.5	64.0	1.5	1.5	4A34		5.42	7.70	67.50	
FAGU206	90934	64.0	65.5	1.5	.9	4A34		6.65	10.55	80.60	
FAGU206	90935	65.5	67.1	1.6	1.4	4A34		7.61	11.66	102.90	
FAGU206	90936	67.1	68.5	1.4	.5	4E4		9.89	16.00	138.20	
FAGU038	90937	11.1	12.2	1.1	1.1	4E4		2.35	5.52	33.30	
FAGU038	90938	12.2	13.7	1.5	1.5	4EA4		1.70	4.13	31.20	
FAGU038	90939	13.7	15.2	1.5	1.5	4E4		4.63	11.80	76.80	
FAGU038	90940	15.2	16.8	1.6	.8	4E4		5.63	15.13	85.70	
FAGU038	90941	16.8	18.3	1.5	1.3	4G0		2.48	6.28	46.30	
FAGU038	90942	18.3	19.8	1.5	1.4	4G4		3.73	10.77	62.40	
FAGU038	90943	19.8	21.3	1.5	1.4	4G4		3.45	7.99	60.30	
FAGU038	90944	21.3	22.9	1.6	1.2	4G4		4.03	9.46	93.90	
FAGU038	90945	22.9	24.4	1.5	1.5	4ED4		6.20	12.50	104.90	
FAGU038	90946	24.4	25.9	1.5	1.5	4E4		5.42	10.15	75.80	
FAGU038	90947	25.9	27.4	1.5	1.5	4AD		4.25	6.02	71.70	
FAGU038	90948	27.4	29.0	1.6	1.6	4A13		.65	1.18	13.00	
FAGU076	90949	27.4	29.3	1.9	1.5	4E4		3.90	5.00	50.40	
FAGU076	90950	29.3	30.5	1.2	1.2	4E4		5.15	7.05	83.70	
FAGU076	90951	30.5	32.0	1.5	1.5	4E4		4.60	5.85	73.70	
FAGU076	90952	32.0	32.8	.8	.8	4E4		6.92	10.21	86.70	
FAGU076	90953	32.8	34.3	1.5	1.4	4E4		4.30	5.10	57.60	
FAGU076	90954	34.3	36.4	2.1	2.0	4D4		12.04	12.77	183.40	
FAGU076	90955	36.4	38.5	2.1	2.0	4CEA		2.70	1.60	40.50	
FAGU076	90956	38.5	41.1	2.6	2.5	4A3		1.95	1.15	32.20	
FAGU076	90957	41.1	42.7	1.6	1.4	4A3		1.20	.25	20.20	
FAGU216	90969	62.8	64.0	1.2	1.2	3GC		1.68	2.80	30.20	
FAGU216	90970	64.0	65.5	1.5	1.5	4E4\$		5.00	6.30	77.80	
FAGU216	90971	65.5	67.1	1.6	1.6	4EA		4.15	6.93	61.40	
FAGU216	90972	67.1	68.6	1.5	1.4	4A1		2.23	2.05	28.50	
FAGU216	90973	68.6	70.1	1.5	1.4	4A1		1.55	1.83	20.20	
FAGU216	90974	70.1	71.6	1.5	1.3	4AE4		5.60	10.17	70.60	
FAGU216	90975	71.6	73.6	2.0	2.0	4EAL		3.50	6.25	52.50	
FAGU216	90976	94.0	96.0	2.0	1.9	4AG		.23	.35	5.10	

DDH	SAMPLE	---DEPTHS---	INT	REC	ROCK	CU	PB	ZN	AG(AA)	AG(FA)
		FROM TO			UNIT	%	%	%	G/MT	G/MT
FAGU216	90977	96.0 97.5	1.5	1.5	4AG		.45	1.20	7.20	
FAGU216	90978	97.5 99.1	1.6	1.4	4AG		.08	.30	2.10	
FAGA022	90979	356.7 357.5	.8	.8	4L2		.47	.40	8.20	
FAGU216	90980	100.6 102.1	1.5	1.4	4AG		.18	.30	3.10	
FAGU216	90981	103.6 105.2	1.6	1.4	4AG		.08	.10	2.10	
FAGU216	90982	105.2 106.7	1.5	1.4	4AG		.08	.43	2.10	
FAGU216	90983	106.7 108.2	1.5	.5	4AE		3.88	7.34	45.30	
FAGU216	90984	108.2 109.7	1.5	1.0	4AO		.30	.88	5.10	
FAGU216	90985	123.3 123.8	.5	.5	4D34		9.40	9.30	90.90	
FAGU216	90986	126.5 128.0	1.5	1.5	4C8		1.88	1.93	18.20	
FAGU216	90987	128.0 129.5	1.5	1.5	4D8		2.75	2.35	30.20	
FAGA027	91000	160.3 160.9	.6	.5	4AG		1.90	2.82		35.30
FAGA027	91001	160.9 162.0	1.1	.9	4A4		2.50	4.50		48.30
FAGA027	91002	162.0 165.2	3.2	3.2	4A4		2.23	4.92		45.30
FAGA027	91003	165.2 168.2	3.0	3.0	4A4		2.78	4.92		47.30
FAGA027	91004	168.2 169.8	1.6	1.5	4A4		3.45	5.64		82.60
FAGA027	91005	169.8 172.1	2.3	2.3	4AG		1.63	3.24		26.40
FAGA027	91006	172.1 175.0	2.9	2.9	4CC		.93	.77		11.00
FAGA027	91007	175.0 177.7	2.7	2.6	4CG		1.14	.89		16.10
FAGA027	91008	177.7 180.7	3.0	3.0	4CO		2.00	2.10		26.40
FAGA027	91009	180.7 183.3	2.6	2.4	4CG		3.08	.88		33.30
FAGA027	91010	183.3 184.5	1.2	1.2	4DO		2.78	3.60		32.20
FAGA027	91011	209.9 212.1	2.2	2.2	4DG		2.35	3.86		35.30
FAGA027	91012	212.1 215.2	3.1	3.0	4CO		2.40	2.28		35.30
FAGA027	91013	215.2 217.3	2.1	2.1	4DO		4.13	3.18		55.50
FAGA027	91014	217.3 219.2	1.9	1.8	4A4		5.10	3.24		68.60
FAGA027	91015	219.2 221.0	1.8	1.8	4A4		5.25	6.48		75.80
FAGA027	91016	221.0 223.0	2.0	2.0	4A4		7.05	10.98		119.00
FAGA027	91017	223.0 225.2	2.2	2.2	4A4		2.50	3.24		44.20
FAGA027	91018	225.2 228.3	3.1	3.0	4CO		1.05	2.22		18.20
FAGA027	91019	228.3 231.3	3.0	3.0	4CO		2.70	3.42		37.40
FAGA027	91020	231.3 234.4	3.1	3.0	4CO		1.23	1.06		18.20
FAGA027	91021	325.6 326.3	.7	.7	4LG		.07	.16		1.00
FAGA069	91022	137.8 138.6	.8	.8	4D4		6.31	8.39	91.90	
FAGA069	91023	160.8 162.2	1.4	.0	4DG		2.43	4.62	35.30	
FAGA069	91024	207.3 209.2	1.9	1.8	4A4		2.30	5.58	44.20	
FAGA069	91025	220.2 221.4	1.2	.9	4AD4		8.58	24.07		111.10
FAGA069	91026	222.9 223.8	.9	.9	4A4		5.74	14.43	105.90	
FAGA069	91027	231.3 232.2	.9	.9	4D4		9.25	19.60	145.00	
FAGA069	91028	312.4 314.2	1.8	1.8	4E4		5.95	9.13	83.60	
FAGA076	91029	139.5 140.5	1.0	.0	4G48		6.70	10.65		62.40
FAGA076	91030	140.5 142.1	1.6	.0	4E4		4.65	7.20		66.50
FAGA076	91031	142.1 143.6	1.5	.0	4A4		3.75	5.28	52.40	
FAGA076	91032	284.5 285.4	.9	.9	4A4		6.94	7.68	91.90	
FAGA076	91033	285.8 287.4	1.6	.0	4D34		5.18	4.92	63.40	
FAGA076	91034	337.8 338.3	.5	.0	4DE4		6.44	11.65		68.60
FAGA076	91035	338.3 339.2	.9	.0	4A10		.02	.06		1.00
FAGA076	91036	341.8 344.0	2.2	.0	4DE		2.35	3.48		35.30
FAGA076	91037	364.8 366.5	1.7	.0	4E46		4.35	4.44		52.40

CDH	SAMPLE	---DEPTHS---		INT	REC	ROCK UNIT	CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT
		FROM	TO								
FAGA076	91038	367.8	369.4	1.6	.0	4GG		3.15	3.06		40.40
FAGA076	91039	369.4	370.6	1.2	.0	4GG		1.00	.31		12.00
FAGA076	91040	370.6	372.2	1.6	.0	4EG		4.73	3.60		48.30
FAGA076	91041	372.2	373.4	1.2	.0	4C3		1.60	.22		9.90
FAGA076	91042	373.4	374.4	1.0	.0	4GG8		5.37	4.20		48.30
FAGA076	91043	374.4	375.7	1.3	.0	4C3		.59	.27		11.00
FAGA076	91044	375.7	377.3	1.6	.0	4GG8		5.03	3.66		50.40
FAGA076	91045	377.3	378.7	1.4	.0	4GG8		4.05	3.42		39.40
FAGA079	91046	89.3	90.8	1.5	1.5	4A4		3.30	5.46		45.30
FAGA079	91047	90.8	92.5	1.7	1.7	4A4		2.93	5.40		37.40
FAGA079	91048	92.5	96.0	3.5	1.4	4A4		4.13	2.82		44.20
FAGA079	91049	96.0	97.4	1.4	1.3	4AC		1.58	1.94		25.40
FAGA079	91050	97.4	99.4	2.0	2.0	4AC		1.35	2.46		23.30
FAGA079	91051	99.4	100.9	1.5	1.5	4A4		2.50	4.26		35.30
FAGA079	91052	100.9	102.4	1.5	.0	4AC		1.48	3.00		21.30
FAGA079	91053	102.4	104.5	2.1	1.8	4A4		1.90	4.14		29.10
FAGA079	91054	106.8	109.7	2.9	2.6	4AQ		.93	1.84		15.10
FAGA079	91055	114.1	115.7	1.6	1.5	4AQ		1.19	3.60		20.20
FAGA079	91056	115.7	116.9	1.2	1.2	4A4		4.50	5.28		60.30
FAGA079	91057	118.1	119.5	1.4	1.3	4D0		2.78	6.48		49.40
FAGA079	91058	119.5	121.7	2.2	2.2	4DE		6.17	10.92		100.80
FAGA079	91059	286.5	287.6	1.1	1.0	4AC		.85	1.74		12.00
FAGA079	91060	287.6	289.4	1.8	1.8	4AD		2.23	4.26		39.40
FAGA079	91061	289.8	291.8	2.0	1.9	4A4		2.28	3.60		36.30
FAGA079	91062	291.8	292.4	.6	.6	4AG		2.33	2.46		28.10
FAGA079	91063	344.6	346.3	1.7	1.6	4E48		5.84	5.40	61.40	
FAGU135	91064	125.5	128.5	3.0	2.9	4L2		.53	1.00		11.00
FAGU135	91065	128.5	131.5	3.0	3.0	4L0		.25	.13		5.10
FAGA069	91066	314.2	315.3	1.1	1.1	4E4		5.48	9.51	82.60	
FAGA052	91072	143.9	146.9	3.0	2.8	4A0		.25	.55	7.20	
FAGA052	91073	146.9	149.0	2.1	2.1	4A0		.18	.44	7.20	
FAGA023	91074	78.0	79.9	1.9	.0	4E4	.12	13.00	20.80	164.00	
FAGA023	91075	79.9	83.1	3.2	.0	4E4	.22	6.47	12.70	101.00	
FAGA023	91076	83.1	84.9	1.8	.0	4A0	.11	1.83	2.25	33.00	
FAGA023	91077	84.9	86.7	1.8	.0	4A4	.06	2.67	4.50	37.00	
FAGA071	91078	120.6	121.6	1.0	1.0	4E4		8.77	18.14		131.00
FAGA071	91079	129.5	130.4	.9	.0	4C0		1.48	2.40		22.30
FAGA026	91081	46.6	49.7	3.1	1.1	4D5		1.55	3.84		25.40
FAGA026	91082	49.7	51.5	1.8	1.8	4D5		2.30	5.16		28.50
FAGA026	91083	55.8	57.8	2.0	2.0	4D5		2.00	3.24		20.20
FAGA026	91084	57.8	59.4	1.6	1.6	4E4		4.13	9.96		100.80
FAGA026	91085	59.4	61.4	2.0	2.0	4E4		5.55	13.20		103.90
FAGA026	91086	62.1	63.7	1.6	1.6	4E4		6.30	14.45		102.80
FAGA026	91087	63.7	65.2	1.5	.0	4E4		6.30	14.45		102.80
FAGA026	91088	65.2	68.0	2.8	2.8	4E4		7.35	15.54		116.90
FAGA026	91089	68.0	69.6	1.6	1.6	4E4		3.30	11.67		51.40
FAGA026	91090	70.4	71.2	.8	.8	4LE		3.15	6.24	51.40	
FAGA026	91091	71.2	72.5	1.3	1.3	4LE		.53	1.44	9.90	
FAGA026	91092	72.5	73.7	1.2	1.1	4LE		3.68	8.04	63.40	

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK UNIT	CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT
		FROM	TO								
FAGA026	91093	73.7	74.5	.8	.0	4LE		6.60	16.30	105.90	
FAGA026	91094	96.5	98.3	1.8	1.8	4A13		1.58	1.06	22.30	
FAGA026	91095	98.3	100.6	2.3	2.2	4A134		3.08	3.72	35.30	
FAGA026	91096	100.6	103.3	2.7	2.6	4A13		.32	.74	6.20	
FAGA026	91097	103.3	105.0	1.7	1.5	4A13		1.38	1.35	17.10	
FAGA026	91098	105.0	106.2	1.2	1.2	4A134		7.05	8.04	97.70	
FAGA026	91099	106.2	109.0	2.8	2.6	4A13		1.35	3.00	20.20	
FAGA128	91100	237.8	239.8	2.0	1.9	4C#8		.93	.65	14.10	
FAGA128	91101	239.8	241.0	1.2	1.2	4E8		2.45	1.63	35.30	
FAGA128	91102	241.0	242.1	1.1	1.1	4G4		6.08	8.00	106.90	
FAGA128	91104	246.2	247.5	1.3	1.1	4D\$		2.23	3.28	28.50	
FAGA128	91105	317.6	318.2	.6	.3	4E0		7.25	8.32	148.10	
FAGA128	91106	318.2	318.8	.6	.5	4J24		15.59	23.00	302.40	
FAGA128	91107	347.8	348.8	1.0	.9	4ED		4.13	4.86	53.50	
FAGA128	91108	352.2	353.6	1.4	1.2	4DA		1.58	1.50	22.30	
FAGA128	91109	353.6	355.1	1.5	1.4	4A10		1.13	1.08	21.30	
FAGA128	91110	355.1	356.6	1.5	1.3	4AD		1.31	1.50	19.20	
FAGA128	91111	356.6	360.0	3.4	2.3	4DAC		3.13	5.40	42.50	
FAGA128	91112	360.0	361.5	1.5	1.3	4C\$		1.65	2.38	26.40	
FAGA128	91113	361.5	362.1	.6	.6	4E4#		8.10	9.68	99.70	
FAGA128	91114	363.0	365.0	2.0	2.0	4G4		5.18	6.16	65.50	
FAGA128	91115	367.1	368.3	1.2	1.2	4E4@		6.74	8.65	100.80	
FAGA128	91116	368.3	370.0	1.7	1.6	4D\$		2.06	2.90	26.40	
FAGA128	91117	419.7	422.3	2.6	2.6	4C0		1.13	2.68	18.20	
FAGA128	91118	425.8	426.8	1.0	1.0	4L\$24		1.33	2.70	20.20	
FAGA128	91119	426.8	428.3	1.5	1.5	4EG		3.08	3.54	51.40	
FAGA128	91120	428.3	429.8	1.5	1.5	4EG		2.70	4.65	43.50	
FAGA128	91121	431.7	433.4	1.7	1.7	4E8		2.56	2.22	27.40	
FAGA128	91122	435.8	436.6	.8	.8	4E4		3.00	3.42	34.30	
FAGA128	91123	436.6	437.6	1.0	1.0	4E4		4.13	2.46	40.40	
FAGA128	91124	437.6	438.6	1.0	1.0	4E4		3.98	3.20	35.30	
FAGA128	91125	438.6	439.6	1.0	1.0	4E4		5.89	6.32	50.40	
FAGA128	91126	444.7	445.9	1.2	1.2	4AG		3.30	2.52	36.30	
FAGA127	91127	93.5	96.5	3.0	2.8	4CA		1.70	2.88	26.40	
FAGA127	91128	96.5	99.5	3.0	2.8	4A4		1.78	4.50	40.40	
FAGA127	91129	99.5	102.5	3.0	2.7	4D5		2.08	5.34	43.50	
FAGA127	91130	102.5	105.5	3.0	.6	4C5		1.68	2.88	25.40	
FAGA127	91131	105.5	108.5	3.0	3.0	4C5		1.20	3.30	26.40	
FAGA127	91132	108.5	111.5	3.0	3.0	4D5		1.38	3.66	25.40	
FAGA127	91133	111.5	114.5	3.0	3.0	4D5		1.68	4.20	38.40	
FAGA127	91134	114.5	117.5	3.0	3.0	4D5		1.78	4.02	35.30	
FAGA127	91135	117.5	120.5	3.0	2.9	4D5		1.58	3.96	29.10	
FAGA127	91136	120.5	123.7	3.2	3.0	4D5		2.15	4.86	38.40	
FAGA127	91137	162.5	165.8	3.3	3.3	4AG		1.28	3.54	23.30	
FAGA127	91138	235.9	237.2	1.3	1.3	4AE		5.61	9.78	85.70	
FAGA127	91139	237.2	240.7	3.5	3.4	4LA		.88	1.06	14.10	
FAGA127	91140	240.7	242.6	1.9	1.9	4A4		2.63	3.54	47.30	
FAGA127	91141	242.6	244.4	1.8	1.8	4D0		3.08	6.88	59.30	
FAGA127	91142	245.4	246.0	.6	.6	4D0		2.30	6.84	48.30	
FAGA127	91143	327.5	329.5	2.0	2.0	4A4		4.73	6.29	76.80	

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK UNIT	CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT
		FROM	TO								
FAGA127	91144	329.5	332.4	2.9	2.5	4A4		3.68	4.56	56.60	
FAGA127	91145	334.2	334.6	.4	.4	4E0		1.10	2.16	20.20	
FAGA127	91146	334.6	336.6	2.0	1.8	4E4		7.13	10.56	126.10	
FAGA127	91147	336.6	337.7	1.1	1.1	4EG		8.78	18.74	146.00	
FAGA127	91148	337.7	339.7	2.0	2.0	4EG		7.65	14.28	98.70	
FAGA127	91149	339.7	341.5	1.8	1.8	4EG		7.20	15.57	96.70	
FAGA127	91150	341.5	343.2	1.7	1.7	4AE		6.78	15.11	98.70	
FAGA127	91151	343.2	345.2	2.0	2.0	4AG		4.73	9.36	74.70	
FAGA127	91152	345.2	347.2	2.0	2.0	4AG		5.85	11.12	87.80	
FAGA127	91153	347.2	348.4	1.2	1.2	4G4		5.40	8.39	102.80	
FAGA127	91154	401.7	402.5	.8	.8	3G916		4.80	5.76	57.60	
FAGA127	91155	402.5	403.4	.9	.9	4G4		5.33	5.16	70.60	
FAGA127	91156	403.4	403.7	.3	.2	3C4\$		.25	.40	8.20	
FAGA127	91157	403.7	404.7	1.0	1.0	4G0		4.43	4.14	75.80	
FAGA127	91158	404.7	406.0	1.3	1.3	4G4		6.38	9.34	106.90	
FAGA127	91159	406.0	408.2	2.2	2.2	4E86		1.78	.88	20.20	
FAGA127	91160	408.2	408.9	.7	.7	4E86		.55	.53	12.00	
FAGA127	91161	408.9	409.6	.7	.7	4E86		7.50	5.67	65.50	
FAGA127	91162	409.6	410.6	1.0	1.0	4E48		5.97	6.59	60.30	
FAGA127	91163	410.6	411.6	1.0	1.0	4C3		.35	.30	12.00	
FAGA127	91164	411.6	412.6	1.0	1.0	4C3		.15	.14	8.90	
FAGA127	91165	412.6	413.6	1.0	1.0	4C3		1.23	.72	23.30	
FAGA127	91166	413.6	414.6	1.0	1.0	4C3		.43	.50	14.10	
FAGA127	91167	414.6	415.6	1.0	1.0	4C3		.48	1.25	16.10	
FAGA127	91168	415.6	416.6	1.0	1.0	4C3		1.18	.90	20.20	
FAGA127	91169	416.6	417.6	1.0	1.0	4C38		.75	.74	17.10	
FAGA127	91170	417.6	419.6	2.0	2.0	4C38		.53	.46	13.00	
FAGA127	91171	419.6	421.1	1.5	1.5	4CEG		1.35	1.54	28.50	
FAGA125	91172	113.8	115.2	1.4	1.3	4AD		3.00	6.85	53.50	
FAGA125	91173	115.2	116.5	1.3	.9	4A5D		.83	1.94	15.10	
FAGA125	91174	116.5	119.2	2.7	2.1	4A4		2.08	4.14	29.10	
FAGA125	91175	119.2	122.2	3.0	2.9	4A4		1.98	4.74	31.20	
FAGA125	91176	122.2	124.4	2.2	2.2	4D5		2.78	4.98	35.30	
FAGA125	91177	124.4	126.6	2.2	2.2	4D5		2.08	3.42	31.20	
FAGA125	91178	133.9	135.1	1.2	1.2	4A4		3.00	5.10	44.20	
FAGA125	91179	172.2	173.6	1.4	1.3	3G91		1.98	3.30	29.10	
FAGA125	91180	173.6	175.0	1.4	1.3	4A4		2.38	5.10	37.40	
FAGA125	91181	175.0	177.7	2.7	2.5	4A4		1.88	4.05	29.10	
FAGA125	91182	227.0	227.7	.7	.7	4A4		3.53	4.30	54.50	
FAGA125	91183	227.7	229.0	1.3	1.3	4AE		6.41	11.84	109.00	
FAGA125	91184	229.5	231.0	1.5	1.5	4AG		.75	1.18	9.90	
FAGA125	91185	317.6	318.6	1.0	1.0	4E14		5.42	6.50	90.80	
FAGA125	91186	321.9	322.8	.9	.5	4D5		2.75	4.50	43.50	
FAGA125	91187	322.8	324.8	2.0	1.9	4D5		3.44	5.55	49.40	
FAGA125	91188	324.8	325.8	1.0	1.0	4C5		1.65	1.66	21.30	
FAGA125	91189	326.6	328.6	2.0	2.0	4A3\$4		2.85	3.98	38.40	
FAGA125	91190	328.6	331.1	2.5	2.5	4A3\$		1.63	2.10	28.50	
FAGA125	91191	336.5	337.6	1.1	1.1	3G6		2.50	2.70	25.40	
FAGA125	91192	340.6	342.6	2.0	1.9	4AD		1.38	2.20	16.10	
FAGA125	91193	344.0	345.6	1.6	1.6	4D45		3.23	4.05	39.40	

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK UNIT	CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT
		FROM	TO								
FAGA125	91194	355.1	355.7	.6	.6	4A3		.83	1.08	16.10	
FAGA125	91195	355.7	356.7	1.0	1.0	4G4		5.18	8.75	85.70	
FAGA125	91196	356.7	357.4	.7	.7	4G4		4.43	7.87	73.70	
FAGA125	91197	357.6	358.6	1.0	1.0	4G0		3.98	5.00	56.60	
FAGA125	91198	358.6	359.6	1.0	1.0	4G0		3.56	5.50	60.30	
FAGA125	91199	359.6	360.9	1.3	1.3	4GA		3.94	6.57	61.40	
FAGA125	91200	361.3	362.3	1.0	.6	4E4		2.38	4.40	40.40	
FAGA125	91201	362.3	363.3	1.0	1.0	4E4		3.60	4.48	55.50	
FAGA125	91202	363.3	364.3	1.0	1.0	4E4		3.30	6.28	50.10	
FAGA125	91203	364.3	365.3	1.0	1.0	4E4		4.28	7.68	73.70	
FAGA125	91204	365.3	366.0	.7	.7	4EG		5.18	7.56	94.60	
FAGA125	91205	381.3	383.3	2.0	2.0	4AG		.48	.52	13.00	
FAGA125	91206	383.3	385.3	2.0	2.0	4AG		.20	.18	12.00	
FAGA125	91207	385.3	386.9	1.6	1.6	4AC		.65	.77	28.50	
FAGA125	91208	386.9	388.2	1.3	1.3	4A43		6.96	9.44	98.70	
FAGA125	91209	388.2	390.2	2.0	2.0	4AG		1.15	1.70	21.30	
FAGA125	91210	390.2	392.6	2.4	2.4	4A7		.38	.62	14.10	
FAGA125	91211	392.6	394.7	2.1	2.1	4ADH		3.83	2.88	46.30	
FAGA125	91212	403.4	405.9	2.5	2.5	4E4		2.85	3.12	42.50	
FAGA123	91213	113.2	115.0	1.8	1.8	4DG		2.38	3.48	37.40	
FAGA123	91214	115.0	116.0	1.0	1.0	4C0		1.83	2.00	24.30	
FAGA123	91215	116.0	118.0	2.0	2.0	4DG		1.93	3.54	26.40	
FAGA123	91216	118.0	120.0	2.0	2.0	4DG		1.90	3.48	29.10	
FAGA123	91217	120.0	122.0	2.0	2.0	4C0		1.75	3.18	26.40	
FAGA123	91218	122.0	124.0	2.0	2.0	4C0		1.99	3.00	28.50	
FAGA123	91219	127.6	128.9	1.3	1.3	4C0		1.84	2.76	29.10	
FAGA123	91220	128.9	130.0	1.1	1.1	4C0		1.48	2.46	24.30	
FAGA123	91221	132.6	134.4	1.8	.5	4C0		1.23	1.66	28.50	
FAGA123	91222	134.4	135.9	1.5	.9	4A4		2.50	4.02	36.30	
FAGA123	91223	135.9	136.8	.9	.7	4A4		2.48	5.40	35.30	
FAGA123	91224	136.8	137.8	1.0	.5	4C5		1.78	2.76	28.50	
FAGA123	91225	137.8	139.3	1.5	1.5	4AC		1.93	2.46	30.20	
FAGA123	91226	139.3	141.4	2.1	1.5	4A4		2.45	3.18	37.40	
FAGA123	91227	141.4	142.3	.9	.8	4A4		2.59	3.90	41.50	
FAGA123	91228	142.3	144.5	2.2	.6	4A4		2.70	4.02	43.50	
FAGA123	91229	144.5	145.4	.9	.9	4C0		3.53	5.93	65.50	
FAGA123	91230	145.4	146.6	1.2	.4	4A4		2.78	4.02	46.30	
FAGA123	91231	150.6	151.5	.9	.9	4Q8		1.23	1.18	21.30	
FAGA123	91232	156.5	158.5	2.0	1.8	4A4		2.50	4.38	40.40	
FAGA123	91233	158.5	160.0	1.5	1.4	4A4		2.78	4.20	44.20	
FAGA123	91234	160.0	160.7	.7	.7	4A0		1.73	2.64	29.10	
FAGA123	91235	188.5	189.4	.9	.8	4D0		1.53	3.48	19.20	
FAGA123	91236	189.4	191.1	1.7	1.7	4D0		2.18	5.40	31.20	
FAGA123	91237	191.6	193.5	1.9	.3	4D0		2.93	5.64	33.30	
FAGA123	91238	193.5	194.5	1.0	.6	4D4		23.00	7.20	50.40	
FAGA123	91239	194.5	195.7	1.2	1.1	4D4		3.75	8.00	63.40	
FAGA123	91240	195.7	196.3	.6	.6	4D0		4.58	4.02	59.30	
FAGA123	91241	196.3	197.6	1.3	1.3	4D0		2.85	2.40	33.30	
FAGA123	91242	197.6	200.1	2.5	1.2	4AC		1.93	2.14	28.50	
FAGA123	91243	200.1	201.5	1.4	1.4	4A4		2.48	5.76	46.30	

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK UNIT	CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT
		FROM	TO								
FAGA123	91244	201.5	203.3	1.8	1.8	4A4		1.88	4.68	34.30	
FAGA123	91245	203.3	204.2	.9	.5	4A4		1.70	4.08	26.40	
FAGA123	91246	204.2	205.5	1.3	1.3	4A4		2.18	1.47	25.40	
FAGA123	91247	209.4	211.2	1.8	1.8	4DG		3.60	3.60	38.40	
FAGA123	91248	229.6	230.7	1.1	1.1	4D0		2.85	6.29	48.30	
FAGA123	91249	230.8	231.9	1.1	1.1	4DG		2.63	4.50	36.30	
FAGA123	91250	231.9	233.5	1.6	1.6	5D4\$		1.23	1.40	18.20	
FAGA123	91251	233.5	234.2	.7	.7	4D4		5.71	7.18	88.80	
FAGA123	91252	234.6	236.1	1.5	1.5	4AG		1.18	1.70	19.20	
FAGA123	91253	236.1	237.6	1.5	1.5	3G0		.58	.76	7.20	
FAGA123	91254	239.1	239.9	.8	.8	4C0		2.38	2.14	33.30	
FAGA123	91255	244.0	246.0	2.0	2.0	4AD		4.65	6.90	68.60	
FAGA123	91256	246.0	248.0	2.0	2.0	4A4		4.73	8.11	77.80	
FAGA123	91257	248.0	250.0	2.0	2.0	4A4		4.20	8.07	64.50	
FAGA123	91258	250.0	251.8	1.8	1.8	5B26		.75	1.54	12.00	
FAGA123	91259	251.8	253.0	1.2	1.2	4A44		7.73	16.75	143.30	
FAGA123	91260	253.0	254.0	1.0	1.0	4A4		2.70	4.02	46.30	
FAGA123	91261	273.1	274.6	1.5	1.5	4E4		5.21	11.86	84.70	
FAGA123	91262	274.6	275.7	1.1	1.1	4E4		6.93	14.44	123.10	
FAGA123	91263	278.0	279.3	1.3	1.3	4A4		2.43	5.64	38.40	
FAGA123	91264	279.3	281.0	1.7	1.7	4D4		5.11	6.05	76.80	
FAGA123	91265	281.0	282.5	1.5	1.5	4AD		3.75	5.86	58.60	
FAGA123	91266	282.5	284.0	1.5	1.5	4A4		4.35	5.64	73.70	
FAGA123	91267	284.0	285.6	1.6	1.5	4A4		4.95	7.58	85.70	
FAGA123	91268	285.6	286.7	1.1	1.1	4A4		3.68	7.69	68.60	
FAGA123	91269	299.1	300.4	1.3	1.3	4A4		2.63	3.42	44.20	
FAGA123	91270	300.4	302.0	1.6	1.3	4C5		1.15	2.10	18.20	
FAGA123	91271	302.0	304.0	2.0	1.9	4AG		1.88	2.76	30.20	
FAGA123	91272	304.0	306.0	2.0	2.0	4A4		3.15	4.92	50.40	
FAGA123	91273	306.0	307.2	1.2	1.2	4A4		3.98	6.23	60.30	
FAGA123	91274	316.3	317.8	1.5	1.5	3G46		.40	1.36	5.10	
FAGA123	91275	317.8	319.4	1.6	1.6	3G46		.38	.95	4.10	
FAGA123	91276	320.6	322.6	2.0	2.0	4L74		.50	.92	8.90	
FAGA123	91277	322.6	324.5	1.9	1.9	4L74		.23	.52	5.10	
FAGA123	91278	374.0	375.2	1.2	1.2	3C4\$		1.68	1.92	25.40	
FAGA123	91279	375.2	376.4	1.2	1.2	4G4		7.65	11.53	126.10	
FAGA123	91280	376.4	377.4	1.0	1.0	4G4		4.95	5.76	68.60	
FAGA123	91281	378.9	380.2	1.3	1.2	4E\$4		3.83	2.10	50.40	
FAGA123	91282	383.4	384.1	.7	.7	4E\$4		7.41	3.18	106.90	
FAGA123	91283	384.8	385.6	.8	.8	4E\$4		2.48	3.48	42.50	
FAGA123	91284	385.6	386.8	1.2	1.2	3C2		.70	1.28	15.10	
FAGA123	91285	390.4	391.7	1.3	1.3	4E0		1.95	3.06	33.30	
FAGA123	91286	391.7	392.9	1.2	1.2	4E4		3.15	3.12	45.30	
FAGA123	91287	392.9	394.6	1.7	1.7	4A43		4.92	8.35	76.80	
FAGA123	91288	399.0	400.2	1.2	1.2	4A30		.65	1.00	29.10	
FAGA123	91289	400.2	402.0	1.8	1.8	4C3		.68	1.44	20.20	
FAGA123	91290	402.8	404.0	1.2	1.2	4EG		3.98	4.86	52.40	
FAGA123	91291	404.0	405.5	1.5	1.5	4E8		1.88	1.92	30.20	
FAGA123	91292	405.5	406.6	1.1	1.1	4G4		6.98	8.87	112.10	
FAGA123	91293	406.6	408.1	1.5	1.5	4G4		6.38	9.36	103.90	

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK UNIT	CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT
		FROM	TO								
FAGA123	91294	421.8	422.9	1.1	1.1	3G16		.45	.46	11.00	
FAGA123	91295	422.9	423.6	.7	.7	4E81		.65	.46	18.20	
FAGA123	91296	423.6	424.7	1.1	1.1	4AG		.55	.64	11.00	
FAGA123	91297	438.8	440.4	1.6	1.6	4HA		1.55	.64	11.00	
FAGA059	91298	258.7	260.5	1.8	1.8	4EA		5.93	11.11	90.80	
FAGA059	91299	260.5	262.1	1.6	1.6	4A4		2.10	4.20	37.40	
FAGA059	91300	262.1	265.2	3.1	3.1	4AG		1.28	2.52	22.30	
FAGA059	91301	265.2	268.2	3.0	3.0	4AC		1.88	3.96	30.20	
FAGA059	91302	268.2	268.9	.7	.7	4C5		1.38	1.38	19.20	
FAGA059	91303	269.8	271.7	1.9	1.9	4AC		1.65	3.18	25.40	
FAGA059	91304	271.7	273.5	1.8	1.8	4D5		2.40	4.02	34.30	
FAGA059	91305	273.5	274.3	.8	.8	4C5		1.23	2.34	17.10	
FAGA059	91306	280.1	283.3	3.2	3.2	5A19		.15	.28	3.10	
FAGA059	91307	283.3	284.0	.7	.7	5A19		.85	1.36	13.00	
FAGA059	91308	284.5	285.3	.8	.8	4AC		.73	1.24	12.00	
FAGA059	91309	285.6	287.2	1.6	1.5	4AG		1.03	1.98	14.10	
FAGA059	91310	287.2	288.6	1.4	1.4	4AC		.66	1.60	8.20	
FAGA059	91311	288.6	290.3	1.7	1.7	4C5		.30	.44	4.10	
FAGA059	91312	308.5	310.4	1.9	1.9	4AC		.49	.94	7.20	
FAGA059	91313	310.4	312.8	2.4	2.2	4AC		.44	1.00	7.20	
FAGA059	91314	312.8	315.0	2.2	2.2	4C5		1.38	2.34	21.30	
FAGA059	91315	315.0	316.2	1.2	1.2	4C0		.65	.95	9.90	
FAGA059	91316	316.2	318.8	2.6	2.6	4C0		.65	1.24	9.90	
FAGA059	91317	318.8	321.9	3.1	2.8	4C0		.65	1.14	9.90	
FAGA059	91318	321.9	323.4	1.5	1.2	4AC		.63	.56	6.20	
FAGA059	91319	323.4	324.7	1.3	1.3	3C4\$		.07	.09	1.00	
FAGA059	91320	324.7	327.1	2.4	2.1	4A4		3.53	6.12	46.30	
FAGA059	91321	327.1	327.8	.7	.7	4A30		1.28	1.40	17.10	
FAGA059	91322	327.8	329.7	1.9	1.9	4A30		.90	.45	20.20	
FAGA059	91323	329.7	331.6	1.9	1.9	4DG		6.15	10.38	100.80	
FAGA059	91324	331.6	333.4	1.8	1.8	4G4		4.95	8.52	90.80	
FAGA059	91325	333.4	335.4	2.0	2.0	4E4		8.43	14.39	104.90	
FAGA059	91326	335.4	336.9	1.5	1.2	4E#4		5.70	11.67	121.00	
FAGA059	91327	336.9	337.5	.6	.6	3C4\$		1.45	2.40	23.30	
FAGA059	91328	337.5	337.8	.3	.3	3C4\$		.14	.72	6.20	
FAGA059	91329	337.8	340.0	2.2	.9	5A6\$		.19	.38	2.10	
FAGA059	91330	340.0	340.3	.3	.3	4E4\$		9.65	16.21	201.60	
FAGA059	91331	340.3	341.0	.7	.5	3G4		.05	.18	6.20	
FAGA059	91332	341.0	341.4	.4	.4	4E46		14.61	19.44	196.80	
FAGA059	91333	341.4	343.1	1.7	1.7	5A6\$		.07	.12	2.10	
FAGA059	91334	343.1	344.5	1.4	1.2	4E46\$		11.00	17.19	176.50	
FAGA059	91335	380.5	381.7	1.2	1.2	4AG		2.33	2.52	53.10	
FAGA059	91336	381.7	382.9	1.2	1.1	4G0		3.00	4.62	68.60	
FAGA059	91337	384.1	384.4	.3	.3	4G4		4.50	8.16	43.50	
FAGA059	91338	384.7	387.2	2.5	2.5	4G4		5.10	8.28	73.70	
FAGA059	91339	387.2	387.6	.4	.4	4L4\$		.68	.40	8.20	
FAGA059	91340	387.6	389.8	2.2	2.2	4G4		6.30	9.41	100.80	
FAGA059	91341	389.8	390.9	1.1	1.1	4G4		5.70	8.52	100.80	
FAGA059	91342	390.9	392.4	1.5	1.4	4G4		5.70	8.64	80.60	
FAGA059	91343	392.4	393.6	1.2	1.2	4L12		2.10	1.84	44.20	

DDH	SAMPLE	----DEPTHS----	INT	REC	ROCK	CU	PB	ZN	AG(AA)	AG(FA)
		FROM TO			UNIT	%	%	%	G/MT	G/MT
FAGA061	91344	240.5 242.2	1.7	1.6	5A6\$		.39	.72	6.20	
FAGA061	91345	242.2 243.2	1.0	1.0	5A6\$		1.40	2.46	17.10	
FAGA061	91346	243.2 244.1	.9	.8	4E14		1.93	4.02	40.40	
FAGA061	91347	244.1 245.3	1.2	1.1	5C4\$		1.05	1.66	11.00	
FAGA061	91348	256.0 257.6	1.6	1.4	4Q43		1.88	2.64	35.30	
FAGA061	91349	264.1 265.8	1.7	1.7	4C0		1.55	1.88	22.30	
FAGA061	91350	265.8 268.6	2.8	2.8	4A0		1.85	3.00	32.60	
FAGA061	91351	268.6 271.6	3.0	3.0	4AC		1.50	1.72	22.30	
FAGA061	91352	271.6 273.5	1.9	1.9	4A0		1.28	1.76	19.20	
FAGA061	91353	273.5 276.4	2.9	2.9	4A0		1.10	1.54	15.10	
FAGA020	91354	325.0 328.0	3.0	3.0	4CA0		1.13	1.04	16.10	
FAGA020	91355	332.5 333.5	1.0	.8	4GE4		4.43	6.21	77.80	
FAGA020	91356	337.7 338.5	.8	.8	4GA		2.08	2.28	53.50	
FAGA020	91357	338.5 340.2	1.7	1.7	4GA		1.63	2.88	32.20	
FAGA020	91358	343.2 344.8	1.6	1.6	4EG		3.38	5.55	67.50	
FAGA020	91359	351.0 352.0	1.0	1.0	4E4		2.78	2.46	45.30	
FAGA020	91360	352.0 353.0	1.0	1.0	4E4		3.00	2.94	35.30	
FAGA020	91361	355.0 356.7	1.7	1.7	4G4		5.03	6.66	78.80	
FAGA020	91362	360.6 361.6	1.0	1.0	4CE4		3.15	6.33	47.30	
FAGA020	91363	362.7 363.9	1.2	1.2	4E4		4.43	7.94	63.40	
FAGA020	91364	363.9 364.7	.8	.8	4E4		2.20	3.18	40.40	
FAGA020	91365	364.7 366.0	1.3	1.3	4C0		1.03	1.94	25.40	
FAGA020	91366	366.0 367.0	1.0	1.0	4C3		1.40	2.22	30.20	
FAGA020	91367	367.0 368.0	1.0	1.0	4C3		1.70	2.94	34.30	
FAGA020	91368	368.0 369.0	1.0	1.0	4C0		1.50	1.60	30.20	
FAGA020	91369	370.0 371.0	1.0	1.0	4D0		3.75	4.32	64.50	
FAGA020	91370	371.0 372.2	1.2	1.2	4H4		3.90	4.02	60.30	
FAGA020	91371	372.2 372.6	.4	.4	4H0		1.90	1.84	46.30	
FAGA020	91372	372.6 374.7	2.1	2.1	4EC		1.75	2.70	32.20	
FAGA020	91373	257.0 258.5	1.5	1.5	5B9	.05	.98	1.74	24.70	
FAGU187	91374	16.8 18.3	1.5	1.4	4A0		.10	.70	4.10	
FAGU187	91375	18.3 19.8	1.5	1.3	4A13		.43	.78	15.10	
FAGU187	91376	19.8 21.3	1.5	1.3	4A13		1.48	2.85	20.20	
FAGU187	91377	21.3 22.9	1.6	1.6	4A13		3.05	3.55	40.50	
FAGU187	91378	22.9 24.4	1.5	1.5	4A13		1.23	1.33	17.10	
FAGU187	91379	24.4 25.9	1.5	1.4	4A13		1.10	1.48	15.10	
FAGU187	91380	25.9 27.4	1.5	1.4	4A13		1.93	1.85	20.20	
FAGU187	91381	27.4 29.0	1.6	1.6	4A13		.98	2.05	31.20	
FAGU187	91382	29.0 30.5	1.5	1.5	4A13		.60	1.33	8.20	
FAGU187	91383	30.5 32.0	1.5	.8	4A13		1.63	2.93	22.30	
FAGU187	91384	32.0 33.5	1.5	1.5	4A13		1.03	1.68	14.10	
FAGU187	91385	33.5 35.1	1.6	1.6	4A13		.33	1.25	9.90	
FAGU187	91386	45.7 47.2	1.5	1.5	4D3		.47	4.90	7.20	
FAGU187	91387	47.2 48.8	1.6	1.6	4C3		.05	1.33	5.10	
FAGU187	91388	48.8 50.3	1.5	1.5	4C3		.03	.93	5.10	
FAGU187	91389	50.3 51.8	1.5	1.3	4C3		.04	2.35	9.90	
FAGU187	91390	51.8 53.3	1.5	.5	4D3		.04	5.00	8.20	
FAGU187	91391	53.3 54.9	1.6	1.4	4C3		.10	2.13	8.90	
FAGU187	91392	54.9 56.4	1.5	1.5	4A0		.09	2.08	12.00	
FAGU187	91393	56.4 57.9	1.5	1.2	4C3		.13	1.95	11.00	

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK UNIT	CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT
		FROM	TO								
FAGU187	91394	57.9	59.4	1.5	.9	4C3		.28	1.80	8.90	
FAGU187	91395	59.4	60.3	.9	.9	4CE		1.95	3.98	42.50	
FAGU208	91396	.0	1.5	1.5	.6	4D4		6.52	8.88	75.80	
FAGU208	91397	1.5	3.0	1.5	1.5	4D4		3.58	7.32	55.50	
FAGU208	91398	3.0	4.6	1.6	1.5	4D4		4.60	6.87	60.30	
FAGU208	91399	4.6	6.1	1.5	1.5	4D4		4.25	8.78	66.50	
FAGU208	91400	6.1	7.5	1.4	1.3	4AD4		2.80	7.47	47.30	
FAGU208	91401	8.5	9.9	1.4	1.3	4EKD		5.00	11.10	68.60	
FAGU208	91402	45.7	47.2	1.5	1.3	4ED4		4.98	6.16	74.70	
FAGU208	91403	47.2	48.8	1.6	1.0	4E4		8.50	15.65	112.10	
FAGU208	91404	48.8	50.3	1.5	1.5	4G4		4.90	8.98	85.70	
FAGU208	91405	50.3	51.8	1.5	1.5	4G4		5.75	8.13	90.90	
FAGU208	91406	51.8	53.3	1.5	1.5	4E4		4.28	4.55	63.40	
FAGU208	91407	53.3	55.5	2.2	2.2	4G4		4.65	7.12	81.60	
FAGU208	91408	55.5	57.1	1.6	1.6	4AQ		1.53	2.68	25.40	
FAGU208	91409	129.8	131.1	1.3	1.3	4E4		3.25	3.20	41.50	
FAGU208	91410	131.1	132.6	1.5	1.5	4EC		1.93	.75	19.20	
FAGU208	91411	132.6	134.1	1.5	1.5	4G4		4.38	5.68	65.50	
FAGU208	91412	134.1	135.6	1.5	1.5	4C8		.58	.93	14.10	
FAGU208	91413	135.6	137.2	1.6	1.6	4C8		.33	.50	8.90	
FAGU208	91414	137.2	138.7	1.5	1.5	4C8		.63	.45	9.90	
FAGU208	91415	138.7	140.2	1.5	1.5	4C8		.65	1.63	9.90	
FAGU209	91416	.0	3.0	3.0	1.4	4D3		4.90	3.55	48.50	
FAGU209	91417	3.0	4.5	1.5	1.5	4D3		4.28	3.08	49.40	
FAGU209	91418	4.5	6.0	1.5	1.5	4D34		4.45	9.52	66.50	
FAGU209	91419	6.0	7.5	1.5	.8	4A4		1.68	5.45	27.40	
FAGU209	91420	7.5	9.0	1.5	.7	4A4		2.55	5.73	39.40	
FAGU209	91421	9.0	10.5	1.5	1.3	4EDK		6.98	10.80	122.10	
FAGU209	91422	13.8	16.8	3.0	1.7	4D4\$		5.33	10.49	89.80	
FAGU209	91423	16.8	18.3	1.5	1.4	4E4\$		6.04	13.42	93.90	
FAGU209	91424	18.3	19.8	1.5	.6	4EGL		3.55	8.91	53.50	
FAGU209	91425	21.3	22.8	1.5	1.4	4D4\$		5.53	9.01	78.90	
FAGU209	91426	22.8	24.3	1.5	1.5	4D4		6.98	13.58	102.90	
FAGU209	91427	24.3	26.0	1.7	1.6	4ED		10.25	19.77	217.40	
FAGU209	91428	33.5	35.1	1.6	1.5	4D4\$		4.70	6.92	65.50	
FAGU209	91429	39.4	41.1	1.7	1.6	4DL		3.90	4.55	52.50	
FAGU209	91430	41.1	42.7	1.6	1.5	4DL		2.78	2.90	40.50	
FAGU209	91431	42.7	44.2	1.5	.7	4E4*		6.23	10.29	131.00	
FAGU209	91432	44.2	45.7	1.5	1.1	4E4*		5.67	8.75	97.70	
FAGU209	91433	45.7	47.2	1.5	1.0	4E4*		6.49	10.25	108.00	
FAGU209	91434	47.2	48.7	1.5	.9	4E4*		4.55	6.41	69.60	
FAGU209	91435	48.7	50.2	1.5	.8	4E4*		3.48	5.30	48.30	
FAGU209	91436	50.2	51.9	1.7	1.0	4AQ		1.05	1.90	16.10	
FAGU210	91437	.0	3.0	3.0	.7	4D54		6.42	4.55	71.70	
FAGU210	91438	3.0	4.5	1.5	1.3	5D4*		.85	2.70	14.10	
FAGU210	91439	4.5	6.0	1.5	1.2	4D4		3.73	8.11	56.60	
FAGU210	91440	6.0	7.5	1.5	1.5	4D4		3.70	7.90	53.50	
FAGU210	91441	7.5	9.0	1.5	.8	5D4*		2.30	4.80	33.30	
FAGU210	91442	9.0	10.5	1.5	1.4	4D45		3.78	6.90	58.60	
FAGU210	91443	10.5	12.0	1.5	1.1	4D5		3.20	6.55	46.30	

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK UNIT	CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT
		FROM	TO								
FAGU210	91444	12.0	13.5	1.5	1.1	5D4*		2.90	5.30	48.30	
FAGU210	91445	13.5	15.0	1.5	1.5	4D45		3.82	9.05	68.60	
FAGU210	91446	15.0	16.5	1.5	1.3	4D45		4.13	9.01	78.90	
FAGU210	91447	16.5	18.0	1.5	1.1	4C5		1.38	3.13	23.30	
FAGU210	91448	18.0	19.5	1.5	.9	4D5		2.88	6.92	50.40	
FAGU210	91449	19.5	21.0	1.5	1.5	4D45		7.83	13.57	125.10	
FAGU210	91450	21.0	22.5	1.5	1.5	4D45		5.00	9.74	80.60	
FAGU210	91451	22.5	24.0	1.5	1.5	4A4		2.63	5.63	42.50	
FAGU210	91452	24.0	25.5	1.5	1.5	5D4*		.53	.25	8.20	
FAGU210	91453	25.5	27.1	1.6	1.5	4A3		1.75	1.48	27.40	
FAGU210	91454	29.8	32.0	2.2	2.2	4E4\$		7.68	16.70	140.20	
FAGU210	91455	36.4	38.4	2.0	1.8	4A4		6.19	7.87	79.50	
FAGU210	91456	59.4	60.9	1.5	1.5	4LDE		6.22	9.59	88.80	
FAGU210	91457	60.9	62.4	1.5	1.5	4E4		4.87	7.52	71.70	
FAGU210	91458	62.4	63.9	1.5	1.5	4E4		5.00	7.70	69.60	
FAGU210	91459	63.9	65.4	1.5	1.5	4AE		5.63	10.60	81.60	
FAGU210	91460	65.4	66.9	1.5	1.1	4AC		1.13	1.45	15.10	
FAGU210	91461	89.9	92.9	3.0	1.7	4AC		.58	.73	13.00	
FAGU210	91462	92.9	94.4	1.5	1.5	4AC		.18	.65	14.10	
FAGU210	91463	94.4	95.9	1.5	1.1	4AC		.15	.28	8.20	
FAGU210	91464	95.9	98.9	3.0	2.1	4AC		.33	1.08	8.20	
FAGU210	91465	98.9	100.4	1.5	1.5	4AC		.73	1.35	13.00	
FAGU210	91466	100.4	101.9	1.5	1.3	4AC		.05	.45	3.10	
FAGU210	91467	101.9	104.9	3.0	2.2	4AC		.05	.33	5.10	
FAGU210	91468	104.9	107.9	3.0	2.9	4AC		.07	1.05	4.10	
FAGU210	91469	107.9	109.9	2.0	2.0	4EC		1.00	1.63	23.30	
FAGU210	91470	113.2	114.4	1.2	1.2	4D45		6.99	12.52	98.70	
FAGU211	91471	1.2	4.6	3.4	1.1	4AC		1.58	2.55	22.30	
FAGU211	91472	4.6	7.6	3.0	1.6	4C5		1.13	.88	14.10	
FAGU211	91473	7.6	9.1	1.5	1.3	4C5		1.68	1.53	20.20	
FAGU211	91474	9.1	10.6	1.5	1.1	4C5		1.03	1.83	14.10	
FAGU211	91475	10.6	13.6	3.0	.9	4C5		.90	.93	9.90	
FAGU211	91476	13.6	16.6	3.0	1.2	4AC		1.53	.75	19.20	
FAGU211	91477	16.6	19.6	3.0	1.1	4A4		4.50	6.55	59.30	
FAGU211	91478	19.6	21.1	1.5	1.0	4A4		1.90	3.35	26.40	
FAGU211	91479	21.1	22.6	1.5	.9	4A4		3.58	7.48	45.30	
FAGU211	91480	22.6	24.1	1.5	.8	4A4		3.93	7.54	51.40	
FAGU211	91481	24.1	25.9	1.8	.8	4AC		1.08	2.95	18.20	
FAGU211	91482	25.9	27.4	1.5	1.5	4E4		8.99	15.07	159.40	
FAGU211	91483	27.4	28.1	.7	.7	4E4		6.43	9.22	110.10	
FAGU211	91484	35.4	36.9	1.5	1.5	4AEG		2.63	4.85	59.30	
FAGU211	91485	36.9	38.4	1.5	1.5	4G4		4.48	8.19	69.60	
FAGU211	91486	38.4	39.5	1.1	1.1	4G4		3.40	7.16	72.70	
FAGU211	91487	39.5	41.0	1.5	1.5	4G4		4.50	7.24	75.80	
FAGU211	91488	41.0	42.5	1.5	1.5	4G4		5.00	7.87	74.70	
FAGU211	91489	42.5	44.3	1.8	1.7	4E4		2.85	3.20	60.30	
FAGU211	91490	71.6	73.1	1.5	1.5	4D4		4.33	6.44	64.50	
FAGU211	91491	73.1	74.6	1.5	1.5	4C3		1.80	2.15	33.30	
FAGU211	91492	74.6	76.1	1.5	1.4	4D53		2.68	4.75	42.50	
FAGU211	91493	76.1	77.6	1.5	1.5	4D53		2.73	2.60	46.30	

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK UNIT	CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT
		FROM	TO								
FAGU211	91494	77.6	79.1	1.5	1.5	4C3		.25	.53	11.00	
FAGU211	91495	79.1	80.6	1.5	1.4	4C3		.40	.80	15.10	
FAGU211	91496	80.6	82.1	1.5	1.4	4C3		.05	.55	9.90	
FAGU211	91497	82.1	83.6	1.5	1.5	4C3		.30	.65	13.00	
FAGU211	91498	83.6	85.1	1.5	1.5	4C3		.25	.65	12.00	
FAGU211	91499	85.1	86.6	1.5	1.5	4C3		.80	2.00	24.30	
FAGU211	91500	86.6	88.1	1.5	1.5	4D4		5.56	6.56	73.70	
FAGU212	91501	10.7	11.2	.5	.5	4A0		1.30	2.73	15.10	
FAGU212	91502	11.2	12.2	1.0	1.0	4C5		1.48	1.93	19.20	
FAGU212	91503	12.2	13.7	1.5	1.5	4C0		2.15	1.60	24.30	
FAGU212	91504	13.7	15.2	1.5	1.3	4D0		3.40	3.00	40.50	
FAGU212	91505	15.2	16.8	1.6	1.5	4DC		2.60	3.55	32.20	
FAGU212	91506	16.8	18.3	1.5	1.2	4C0		2.23	2.75	28.50	
FAGU212	91507	18.3	19.8	1.5	1.5	4C0		1.68	2.65	20.20	
FAGU212	91508	19.8	21.3	1.5	1.5	4C0		.40	.63	5.10	
FAGU212	91509	21.3	22.9	1.6	1.0	4C0		1.48	2.00	20.20	
FAGU212	91510	30.0	32.0	2.0	2.0	4C0		.50	.78	8.20	
FAGU212	91511	32.0	33.5	1.5	1.5	4A0		.33	1.18	6.20	
FAGU212	91512	33.5	36.0	2.5	2.5	4A4		1.88	3.73	29.10	
FAGU212	91513	36.0	38.1	2.1	2.0	4E4		8.05	15.78	119.00	
FAGU212	91514	41.9	42.7	.8	.8	4E46		7.39	9.26	114.50	
FAGU212	91515	42.7	44.2	1.5	1.5	4E46		5.75	6.01	119.00	
FAGU212	91516	44.2	45.7	1.5	1.5	4E46		4.53	7.53	87.80	
FAGU212	91517	45.7	47.2	1.5	1.5	4G4		4.68	8.60	68.60	
FAGU212	91518	47.2	48.8	1.6	1.6	4G4		5.30	8.88	81.60	
FAGU212	91519	48.8	50.3	1.5	1.5	4G0		2.56	5.89	41.50	
FAGU212	91520	50.3	51.8	1.5	1.5	4G4		3.70	6.65	59.30	
FAGU212	91521	51.8	53.3	1.5	1.0	4E4		4.95	7.30	68.60	
FAGU212	91522	54.9	56.4	1.5	.8	4E4		3.15	6.06	51.40	
FAGU212	91523	56.4	59.1	2.7	1.0	4E46		4.20	8.04	80.60	
FAGU212	91524	59.1	61.0	1.9	1.9	4E04		6.29	12.70	93.90	
FAGU212	91525	61.0	62.5	1.5	1.5	4E4\$		4.00	3.60	57.60	
FAGU212	91526	62.5	64.0	1.5	1.5	4EGD		9.15	15.98	118.60	
FAGU212	91527	64.0	65.5	1.5	1.5	4E4\$		3.85	4.15	46.30	
FAGU212	91528	65.5	67.1	1.6	1.5	4E0\$		2.80	1.70	39.80	
FAGU212	91529	67.1	68.6	1.5	1.4	4E4*		7.58	14.12	127.90	
FAGU212	91530	68.6	70.2	1.6	1.5	4E4*		3.38	3.80	47.30	
FAGU213	91531	51.2	52.7	1.5	1.1	4E4		3.83	6.86	63.40	
FAGU213	91532	52.7	54.2	1.5	1.2	4E4#		2.58	4.45	41.50	
FAGU213	91533	54.2	55.7	1.5	1.4	4E4#		4.23	7.70	58.60	
FAGU213	91534	55.7	57.2	1.5	1.1	4G0		3.23	6.12	54.50	
FAGU213	91535	57.2	58.7	1.5	1.2	4EG4		4.08	7.05	71.70	
FAGU213	91536	58.7	60.2	1.5	.9	4E4#		5.97	9.17	94.60	
FAGU213	91537	60.2	61.7	1.5	.9	4EG4		3.85	6.70	50.40	
FAGU213	91538	61.7	63.2	1.5	.9	4EG4		5.79	8.39	78.90	
FAGU213	91539	63.2	64.7	1.5	1.1	4E0#		1.50	1.63	31.20	
FAGU213	91540	64.7	66.2	1.5	.8	4E0#		1.28	1.20	30.20	
FAGU213	91541	66.2	67.7	1.5	1.0	4E4#		2.75	4.60	52.50	
FAGU213	91542	67.7	69.2	1.5	1.1	4E0#		1.53	2.45	28.50	
FAGU213	91543	69.2	70.7	1.5	1.0	4A34		2.93	5.00	46.30	

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK UNIT	CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT
		FROM	TO								
FAGU213	91544	70.7	72.2	1.5	1.0	4A30		.85	1.53	17.10	
FAGU213	91545	72.2	73.7	1.5	.7	4A34		1.83	4.40	24.30	
FAGU213	91546	73.7	75.2	1.5	.9	4AG		.85	1.83	13.00	
FAGU213	91547	75.2	76.7	1.5	.9	4AG		.83	1.03	16.10	
FAGU213	91548	76.7	78.2	1.5	1.0	4AG		1.10	1.88	27.40	
FAGU213	91549	78.2	79.7	1.5	1.0	4AE		9.14	15.62	120.00	
FAGU213	91550	79.7	81.2	1.5	1.0	4AE		4.58	8.31	68.60	
FAGU213	91551	81.2	82.7	1.5	1.3	4AG		.88	1.38	28.10	
FAGU213	91552	82.7	84.2	1.5	1.3	4AG		.18	.80	12.00	
FAGU213	91553	84.2	85.7	1.5	1.3	4DE4		6.37	13.89	88.80	
FAGU213	91554	85.7	87.2	1.5	1.3	4A43		5.70	11.23	70.60	
FAGU213	91555	87.2	88.7	1.5	1.5	4A43		2.43	4.45	33.30	
FAGU213	91556	88.7	90.2	1.5	1.5	4A31		.68	1.30	20.20	
FAGU213	91557	90.2	91.7	1.5	1.4	4A31		.45	1.28	17.10	
FAGU213	91558	91.7	93.2	1.5	1.3	4A31		.30	1.00	13.00	
FAGU213	91559	93.2	94.7	1.5	1.3	4A31		.18	.98	12.00	
FAGU213	91560	94.7	96.2	1.5	1.5	4A31		.20	1.28	6.20	
FAGU213	91561	96.2	97.7	1.5	1.5	4A31		.88	1.68	12.00	
FAGU213	91562	97.7	99.2	1.5	1.4	4A31		.43	2.53	11.00	
FAGU213	91563	99.2	100.7	1.5	1.0	4A31		.05	.85	9.90	
FAGU213	91564	100.7	102.2	1.5	1.0	4A31		.05	1.03	9.90	
FAGU213	91565	102.2	103.7	1.5	1.5	4C3		.02	.43	8.90	
FAGU213	91566	103.7	105.2	1.5	1.5	4EG		.03	1.00	7.90	
FAGU213	91567	105.2	106.7	1.5	1.5	4AG		.02	.75	5.10	
FAGU213	91568	106.7	108.9	2.2	2.2	4E10		1.28	1.63	29.10	
FAGU213	91569	113.9	114.7	.8	.8	4G4		6.75	12.22	88.80	
FAGU208	91570	33.0	34.0	1.0	.9	3G0		1.85	4.88	27.40	
FAGU209	91571	57.9	59.4	1.5	.0	4A0		1.98	2.83	22.30	
FAGU100	91572	24.4	25.9	1.5	1.5	4A4		2.78	4.55		36.30
FAGA067	91573	284.1	285.0	.9	.0	4E64		4.13	5.88	60.00	
FAGA067	91574	182.8	184.9	2.1	.0	4A14		2.33	3.90	34.00	
FAGA067	91575	186.5	189.0	2.5	.0	4A14		2.18	4.26	33.00	
FAGA067	91576	194.2	196.0	1.8	.0	4A14		2.15	4.62	35.00	
FAGA078	91577	51.7	53.2	1.5	-.5	4D4		5.40	9.22	90.80	
FAGA078	91578	54.6	55.3	.7	-.5	4D4		6.38	13.30	90.80	
FAGA078	91579	56.8	58.0	1.2	-.5	4D4		3.90	8.04	59.70	
FAGA078	91580	74.6	76.1	1.5	-.5	4D47		5.03	4.80	65.50	
FAGA078	91581	78.6	80.8	2.2	-.5	4D45		8.72	14.83	126.10	
FAGA078	91582	80.8	82.6	1.8	-.5	4A4		2.45	4.14	37.40	
FAGA078	91583	82.6	84.0	1.4	-.5	4D4		3.90	6.84	54.50	
FAGA078	91584	84.0	85.3	1.3	-.5	4A4		1.68	4.20	28.10	
FAGA078	91585	85.3	86.0	.7	-.5	4A0		1.83	3.00	27.10	
FAGA078	91586	262.7	263.9	1.2	-.5	4G4		5.10	5.40	64.50	
FAGA078	91587	264.1	264.9	.8	-.5	4L42		1.83	3.18	25.40	
FAGA078	91588	265.2	266.7	1.5	-.5	4L42		1.23	3.00	20.20	
FAGA078	91589	266.7	267.6	.9	-.5	4E4		3.75	6.36	75.80	
FAGA078	91590	284.1	286.1	2.0	-.5	4A43		5.25	7.20	89.80	
FAGA078	91591	286.1	287.4	1.3	-.5	4A30		1.50	3.00	20.20	
FAGA078	91592	287.4	289.0	1.6	-.5	4A34		1.88	3.24	24.30	
FAGA078	91593	289.0	290.2	1.2	-.5	4A34		1.90	3.72	26.10	

DDH	SAMPLE	---DEPTHS---	INT	REC	ROCK	CU.	PB	ZN	AG(AA)	AG(FA)
		FROM TO			UNIT	%	%	%	G/MT	G/MT
FAGA078	91594	290.2 291.4	1.2	-.5	4A30		1.15	1.18	20.20	
FAGA078	91595	291.4 293.5	2.1	-.5	4A34		1.80	4.38	31.20	
FAGA078	91596	293.5 294.1	.6	-.5	4LC		.59	.94	8.20	
FAGA082	91597	97.5 98.3	.8	.0	4D7		2.78	5.04	20.20	
FAGA082	91598	102.2 103.9	1.7	.0	4CG		1.80	3.06	28.50	
FAGA082	91599	103.9 105.2	1.3	.0	4DQ		1.98	3.42	28.50	
FAGA082	91600	118.7 120.7	2.0	.0	4E4		6.15	10.37	91.90	
FAGA082	91601	121.8 123.4	1.6	.0	4DC		2.08	3.30	44.20	
FAGA082	91602	123.4 124.9	1.5	.0	4DQ		2.05	3.12	44.20	
FAGA082	91603	137.1 138.9	1.8	.0	4AE		3.30	6.45	41.50	
FAGA082	91604	273.4 274.1	.7	.0	4G4		4.72	9.40	90.80	
FAGA082	91605	292.2 293.7	1.5	.0	4A4		3.53	4.44	54.50	
FAGA082	91606	293.7 295.2	1.5	.0	4A4		2.23	4.44	33.30	
FAGA082	91607	320.7 322.2	1.5	.0	4E46		4.92	6.35	72.70	
FAGA082	91608	327.2 328.7	1.5	.0	4E48		4.28	3.18	45.30	
FAGA082	91609	328.7 330.3	1.6	.0	4DQ		3.98	1.34	40.40	
FAGA082	91610	330.3 331.8	1.5	.0	4E81		1.38	1.86	16.10	
FAGA082	91611	331.8 333.3	1.5	.0	4E81		1.34	1.56	19.20	
FAGA026	92000	128.5 129.5	1.0	1.0	4A4		3.98	4.20	64.50	
FAGA026	92001	129.5 131.8	2.3	2.0	4AG		1.50	1.43		28.50
FAGA026	92002	131.8 134.7	2.9	2.9	4E1		2.33	2.40		41.50
FAGA026	92003	134.7 137.8	3.1	3.1	4E14		4.73	4.02		65.50
FAGA026	92004	137.8 140.8	3.0	3.0	4E14		3.08	2.88		48.30
FAGA026	92005	140.8 143.9	3.1	3.1	4E1		1.33	2.28		27.40
FAGA026	92006	143.9 144.8	.9	.9	4E14		3.00	3.54		46.30
FAGA026	92007	144.8 147.1	2.3	.6	4E14		2.08	3.48		35.30
FAGA026	92008	208.7 209.5	.8	.0	4D4		4.95	6.84	80.60	
FAGA026	92009	210.4 211.7	1.3	.0	4D4		4.13	5.52	73.70	
FAGA028	92010	50.6 51.1	.5	.4	5DQ		.84	.84		15.10
FAGA028	92011	242.3 244.0	1.7	1.7	4L15		.12	.09		5.10
FAGA028	92012	248.7 250.2	1.5	1.5	4L1		.05	.08		1.00
FAGA058	92013	157.0 157.9	.9	.8	5C4*		.03	.13		2.10
FAGA058	92014	159.7 160.6	.9	.2	4LC		.15	.03		5.10
FAGA058	92015	160.6 164.0	3.4	.1	4LC		.22	.46		4.10
FAGA058	92016	164.0 165.8	1.8	1.4	4LQ		.18	.25		1.00
FAGA065	92017	125.6 126.5	.9	.9	4G4		10.50	10.11		115.90
FAGA065	92018	126.5 128.0	1.5	.6	4G#4		6.00	5.64		74.70
FAGA065	92019	128.0 128.9	.9	.4	4G#4		4.80	2.46		58.60
FAGA065	92020	128.9 130.5	1.6	1.0	4G#4		8.42	5.40		94.60
FAGA065	92021	130.5 132.2	1.7	1.4	4G#4		6.53	3.78		84.70
FAGA065	92022	164.3 165.2	.9	.2	4A14		3.75	1.56	37.40	
FAGA065	92023	165.2 167.6	2.4	.2	4A14		4.20	1.54	40.40	
FAGA083	92024	138.2 140.8	2.6	2.6	4E4		5.20	3.66		72.70
FAGA083	92025	141.3 144.3	3.0	3.0	4E4		3.53	3.12		44.20
FAGA151	92026	110.2 112.4	2.2	.0	5D6		.50	.75	8.91	
FAGA151	92027	112.4 113.4	1.0	.0	4D4		4.15	9.05	80.57	
FAGA151	92028	113.4 115.2	1.8	.0	4AD		1.80	3.35	33.26	
FAGA151	92029	122.5 123.4	.9	.0	4AG		1.40	2.65	21.26	
FAGA151	92030	123.4 124.9	1.5	.0	4A4		3.15	7.42	48.34	

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK UNIT	CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT
		FROM	TO								
FAGA151	92031	124.9	126.0	1.1	.0	4A0		.34	.60	6.17	
FAGA151	92032	129.9	133.2	3.3	.0	3G0		1.70	2.53	24.34	
FAGA029	92033	368.5	371.2	2.7	2.5	4A4		.93	2.22	9.94	
FAGA029	92034	371.2	374.2	3.0	3.0	4A0		1.23	2.22	18.16	
FAGA029	92035	374.2	375.3	1.1	1.0	5C\$		.65	1.28	7.20	
FAGA029	92036	375.3	377.6	2.3	2.3	4A0		1.65	2.58	14.05	
FAGA029	92037	377.6	379.1	1.5	1.2	4C5		.80	1.42	9.94	
FAGA029	92038	379.1	382.2	3.1	3.1	4AC		1.18	1.46	15.00	
FAGA029	92039	385.7	388.6	2.9	2.8	4A0		1.44	2.40	24.34	
FAGA029	92040	388.6	391.6	3.0	3.0	4A0		1.23	2.00	16.11	
FAGA029	92041	391.6	393.9	2.3	2.2	4AD		2.00	4.00	17.14	
FAGA029	92042	403.6	405.0	1.4	1.3	4C0		1.28	2.94	22.28	
FAGA029	92043	406.6	407.9	1.3	1.0	4A4		1.80	4.20	37.37	
FAGA029	92044	407.9	408.4	.5	.4	4A4		2.28	4.92	44.22	
FAGA029	92045	408.4	409.9	1.5	1.0	4A4		2.50	4.80	42.51	
FAGA029	92046	409.9	411.4	1.5	1.5	4A4		1.93	4.20	32.22	
FAGA029	92047	411.4	413.3	1.9	.3	4A0		2.48	1.36	30.17	
FAGA029	92048	413.3	414.5	1.2	1.2	4A4		2.33	5.10	30.17	
FAGA029	92049	436.0	436.8	.8	.7	5A6		.22	.41	5.14	
FAGA029	92050	436.8	438.6	1.8	1.7	4AE		3.68	16.67	80.56	
FAGA029	92051	438.6	439.0	.4	.4	4A4		1.35	5.40	21.25	
FAGA029	92052	439.0	439.8	.8	.7	4A4		1.30	3.84	22.28	
FAGA029	92053	441.9	442.9	1.0	.9	5A6		.58	1.60	12.00	
FAGA064	92054	320.8	322.1	1.3	1.3	4QAC		.85	1.68	7.20	
FAGA064	92055	322.8	324.9	2.1	2.0	4A0		1.13	1.80	15.08	
FAGA064	92056	369.1	372.1	3.0	.6	4L74		1.10	2.34	15.08	
FAGA064	92057	385.6	387.0	1.4	1.4	4A0		1.43	2.58	15.08	
FAGA064	92058	387.0	389.2	2.2	2.1	4A0		1.33	2.40	15.08	
FAGA064	92059	390.9	392.7	1.8	1.0	4A0		1.70	2.88	18.17	
FAGA064	92060	392.7	394.2	1.5	1.5	4A4		2.50	6.42	29.14	
FAGA064	92061	394.2	395.7	1.5	1.5	4A4		3.60	8.77	51.42	
FAGA064	92062	395.7	397.3	1.6	1.5	4A4		2.13	5.25	39.42	
FAGA064	92063	397.3	398.8	1.5	1.2	4A4		1.63	4.80	25.37	
FAGA086	92064	376.5	379.7	3.2	3.2	3G6		.43	.33	4.11	
FAGA086	92065	379.7	380.8	1.1	1.0	4E1		2.25	3.48	30.17	
FAGA086	92066	380.8	383.0	2.2	2.2	4A4		2.08	4.14	31.19	
FAGA086	92067	383.0	384.5	1.5	1.5	4A0		1.58	2.70	23.31	
FAGA086	92068	384.5	385.9	1.4	1.4	4A0		1.78	3.18	25.37	
FAGA086	92069	385.9	387.0	1.1	1.0	4A0		1.65	2.94	24.34	
FAGA086	92070	387.0	388.9	1.9	1.8	4D0		1.60	4.62	21.25	
FAGA086	92071	388.9	391.8	2.9	2.9	4E1					
FAGA086	92072	392.4	393.3	.9	.9	4E1					
FAGA086	92073	393.9	398.0	4.1	4.1	4E0					
FAGA086	92074	508.8	509.7	.9	.0	4Q\$43		3.75	4.68	34.28	
FAGA097	92075	19.1	20.4	1.3	1.3	4L67		1.40	1.54	30.17	
FAGA097	92076	20.4	22.4	2.0	2.0	4L67		.50	.38	30.17	
FAGA097	92077	22.4	23.5	1.1	1.0	4L6		.10	.18	8.23	
FAGA098	92078	24.2	26.8	2.6	2.6	4DEG		2.70	2.64	35.31	
FAGA161	92079	61.6	63.3	1.7	.5	4A0		.90	1.48	14.74	
FAGU073	92080	38.5	39.2	.7	.6	4A4		7.59	17.61	55.54	

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK UNIT	CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT
		FROM	TO								
FAGU073	92081	39.2	41.9	2.7	2.7	4AG		.78	1.62	12.00	
FAGU077	92082	163.0	163.7	.7	.7	4L0		1.50	1.78	22.29	
FAGU099	92083	49.2	50.6	1.4	1.4	4EA		4.09	5.78	62.40	
FAGU107	92084	.0	3.0	3.0	1.2	4DE		1.78	2.60	28.46	
FAGA127	92085	89.4	90.5	1.1	1.0	4C0		1.88	2.94	23.31	
FAGU116	92086	7.1	9.2	2.1	1.4	4L0		.01	.08		
4567506	92087	76.5	77.4	.9	.0	4C5	.02	.18	.21		
4567506	92088	77.4	78.6	1.2	.0	4L14	.06	.43	.47		
4567506	92089	78.6	79.9	1.3	.0	4L14	.04	.20	.29		
4567506	92090	79.9	81.4	1.5	.0	4L14	.05	.87	.86		
4567506	92091	98.8	101.8	3.0	.0	4L0	.02	.01	.01		
4567506	92092	101.8	105.5	3.7	.0	4L0	.02	.01	.01		
4567506	92093	105.5	108.8	3.3	.0	4L0	.02		.01		
4567506	92094	108.8	111.9	3.1	.0	4L0	.02	.01	.01		
4567506	92095	111.9	118.0	6.1	.0	4L0	.02	.01	.01		
4567506	92096	118.0	122.2	4.2	.0	4L0	.02		.01		
4567506	92097	122.2	126.2	4.0	.0	4L0	.02		.01		
4567506	92098	126.2	128.6	2.4	.0	4L0	.02		.02		
4567506	92099	135.0	138.1	3.1	.0	3G84	.03		.01		
4567506	92100	138.1	141.1	3.0	.0	3G4L	.02	.02	.02		
4567506	92101	151.3	151.9	.6	.0	4C0	.07	.02	.01		
4567506	92102	154.2	157.3	3.1	.0	3G8	.02	.02	.02		
4567507	92103	90.4	90.6	.2	.0	4A4#	.02	1.48	3.48		
4567507	92104	90.6	91.4	.8	.0	4D5	.14	2.85	4.38		
4567507	92105	91.4	91.6	.2	.0	4L13	.03	.03	.04		
4567507	92106	91.6	92.4	.8	.0	4L13	.02		.02		
4567507	92107	92.4	93.6	1.2	.0	4L0	.10	.56	.51		
4567507	92108	93.6	94.2	.6	.0	4E4	.07	6.57	7.03		
4567507	92109	94.2	94.6	.4	.0	4C0	.08	.65	.42		
4567507	92110	94.6	95.3	.7	.0	4L43	.02	.03	.04		
4567507	92111	95.3	95.5	.2	.0	4D0	.10	.78	.63		
4567507	92112	95.5	95.7	.2	.0	4D0	.03		.04		
4567507	92113	95.7	96.9	1.2	.0	4DH	.13	2.03	3.24		
4567507	92114	96.9	97.1	.2	.0	4C0	.07	6.32	7.99		
4567507	92115	97.1	98.0	.9	.0	4C0	.15	.50	.33		
4567507	92116	152.4	154.2	1.8	.0	3G8	.07	.02	.04		
4567507	92117	154.2	154.7	.5	.0	5A19	.02	.18	.27		
4567507	92118	154.7	154.8	.1	.0	4L13	.04	.02	.04		
4567507	92119	154.8	155.3	.5	.0	4L13	.18	.06	.03		
4567507	92120	155.3	156.4	1.1	.0	3G84	.03	.02	.02		
4567507	92121	156.4	157.1	.7	.0	4L41	.12	.02	.01		
4567507	92122	157.1	157.9	.8	.0	4L41	.17	.01	.01		
4567507	92123	157.9	159.4	1.5	.0	4L41	.17		.01		
4567507	92124	159.4	161.0	1.6	.0	4L0	.08	.01	.01		
4567507	92125	161.0	162.4	1.4	.0	4L0	.02		.01		
4567509	92126	436.2	436.7	.5	.5	4A4	.07	1.90	4.08		
4567509	92127	436.7	437.8	1.1	1.0	4AG	.07	1.25	1.78		
4567509	92128	438.4	439.5	1.1	1.0	4AG	.02	.05	.07		
4567509	92129	439.6	441.3	1.7	1.7	4AG	.02	.14	.10		
4567509	92130	441.9	443.0	1.1	1.0	4AG	.02	.46	.60		

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK UNIT	CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT
		FROM	TO								
4567509	92131	444.7	445.0	.3	.3	4E4	.34	3.15	11.10		
4567509	92132	445.7	446.0	.3	.2	4H3	.04	1.50	1.78		
4567509	92133	446.0	446.2	.2	.2	4A0	.03	.35	.60		
4567509	92134	446.2	446.5	.3	.3	4H3	.04	3.08	4.56		
4567509	92135	447.8	448.0	.2	.2	4D0	.05	3.38	5.52		
4567509	92136	448.0	449.3	1.3	1.3	4C0	.08	1.01	1.02		
4567509	92137	449.3	450.6	1.3	1.2	4C0	.06	.53	.74		
4567509	92138	450.6	452.5	1.9	1.8	4C0	.06	.38	.72		
4567509	92139	452.7	453.2	.5	.5	4C0	.07	.43	.50		
4567509	92140	453.4	455.2	1.8	1.7	5B6	.03	.10	.07		
4567509	92141	466.0	466.2	.2	.2	4C0	.03	1.03	1.66		
4567509	92142	466.6	468.6	2.0	2.0	4L0	.03	.53	1.14		
4567509	92143	468.6	469.6	1.0	.9	5B4	.06	.38	.25		
4567509	92144	469.6	470.9	1.3	1.2	5B4	.05	.26	.39		
4567509	92145	472.0	472.1	.1	.1	4D0	.08	1.73	5.59		
FAGU006	92146	15.2	18.5	3.3	3.3	4A14		1.93	3.65	37.70	
FAGU006	92147	18.5	19.4	.9	.9	4A14		1.78	3.50	38.70	
FAGU025	92148	61.0	62.5	1.5	1.2	4C0		.88	2.85	14.06	
FAGA134	92149	163.2	163.7	.5	.5	5D4*		.63	1.68	10.97	
FAGU001	92150	.0	2.0	2.0	1.8	4A4		3.98	5.89		55.53
FAGU001	92151	2.0	4.0	2.0	1.8	4A4		4.17	4.60		54.51
FAGU001	92152	4.0	6.0	2.0	1.9	4A4		4.28	6.45		62.39
FAGU001	92153	6.0	8.0	2.0	1.9	4A4		4.05	9.45		63.42
FAGU001	92154	8.0	9.0	1.0	1.0	4A4		4.09	6.90		57.59
FAGU001	92155	14.0	15.0	1.0	.8	4D4		9.26	15.00		129.24
FAGU001	92156	15.0	17.3	2.3	1.5	4K4*		3.38	10.46		55.53
FAGU001	92157	17.3	18.8	1.5	1.4	4K4*		8.50	17.22		111.07
FAGU001	92158	44.1	45.7	1.6	.2	4E4		8.35	12.52		139.18
FAGU001	92159	45.7	47.2	1.5	.7	4E4		8.15	14.81		115.87
FAGU001	92160	47.2	48.8	1.6	1.2	4E4		6.79	13.74		109.01
FAGU001	92161	48.8	50.3	1.5	1.3	4AE4		7.56	12.16		97.70
FAGU001	92162	51.8	53.3	1.5	.3	4E4		7.99	10.07		164.89
FAGU001	92163	53.3	54.9	1.6	.8	4EG4		8.85	14.60		129.24
FAGU074	92164	56.5	57.9	1.4	1.2	4A134		3.38	3.52		44.23
FAGU074	92165	57.9	59.2	1.3	1.3	4A13		.85	1.40		13.03
FAGU074	92166	59.2	60.5	1.3	1.3	4A134		3.33	5.40		35.31
FAGU074	92167	60.5	61.6	1.1	1.1	4A13		1.72	1.85		23.31
FAGU074	92168	67.9	69.3	1.4	1.4	4C3		.11	.68		10.97
FAGU074	92169	69.3	70.6	1.3	1.3	4C3		.12	.45		8.91
FAGU074	92170	70.6	71.9	1.3	1.3	4C3		.32	1.20		17.14
FAGU074	92171	71.9	73.1	1.2	1.2	4C3		.70	1.15		6.17
FAGU074	92172	73.1	74.5	1.4	1.4	4C3		.05	.73		8.23
FAGU074	92173	74.5	75.7	1.2	1.2	4C3		.80	1.90		30.17
FAGU074	92174	75.7	77.0	1.3	1.3	4C3		.49	1.73		23.31
FAGU074	92175	77.0	78.6	1.6	1.4	4C3		.45	1.58		21.26
FAGU074	92176	78.6	79.9	1.3	1.3	4C3		.48	1.40		16.11
FAGU074	92177	79.9	81.5	1.6	1.6	4C3		.09	.60		10.97
FAGU074	92178	81.5	82.8	1.3	1.3	4C3		.49	2.33		15.09
FAGU074	92179	82.8	84.3	1.5	1.5	4C3		.08	.45		7.20
FAGU074	92180	84.3	85.6	1.3	1.3	4C3		.07	.68		7.20

DDH	SAMPLE	---DEPTHS---	INT	REC	ROCK	CU	PB	ZN	AG(AA)	AG(FA)
		FROM TO			UNIT	%	%	%	G/MT	G/MT
FAGU074	92181	85.6 86.8	1.2	1.2	4C3		.10	.67		8.91
FAGU074	92182	86.8 88.2	1.4	1.4	4C3		.08	.58		8.91
FAGU074	92183	88.2 91.4	3.2	3.2	4C3		.50	.75		17.14
FAGU074	92184	96.8 97.5	.7	.7	4A0		.62	1.00		28.46
FAGU074	92185	103.1 104.5	1.4	.0	4L124		1.67	2.28		26.40
FAGU074	92186	104.5 105.9	1.4	.0	4L124		2.25	2.78		34.29
FAGU080	92187	.0 1.5	1.5	.8	4E15		.82	.35		34.29
FAGU080	92188	1.5 3.0	1.5	1.4	4AE1		2.45	1.05		52.46
FAGU080	92189	3.0 4.6	1.6	1.6	4A13		1.98	1.10		50.40
FAGU080	92190	4.6 5.5	.9	.8	4A13		.80	.59		21.26
FAGU080	92191	6.4 7.6	1.2	1.2	4C0		.23	4.00		8.91
FAGU080	92192	7.6 9.1	1.5	1.5	4C0		.40	2.83		15.09
FAGU080	92193	9.1 10.7	1.6	1.6	4D53		.83	4.70		21.26
FAGU080	92194	10.7 12.2	1.5	1.5	4D53		2.05	5.00		39.43
FAGU080	92195	12.2 13.7	1.5	1.4	4D0		1.52	3.88		28.46
FAGU080	92196	13.7 15.2	1.5	1.2	4D0		1.77	5.65		28.46
FAGU080	92197	15.2 16.8	1.6	1.2	4DA4		5.20	7.11		72.69
FAGU080	92198	16.8 18.3	1.5	1.4	4A134		2.40	5.15		37.37
FAGU080	92199	18.3 19.8	1.5	1.3	4A134		2.10	4.38		34.29
FAGU080	92200	19.8 21.3	1.5	1.2	4A134		2.10	2.88		30.17
FAGU080	92201	21.3 22.9	1.6	1.5	4A13		1.00	2.55		16.11
FAGU080	92202	22.9 24.4	1.5	1.5	4C0		1.29	2.43		21.26
FAGU080	92203	24.4 25.9	1.5	1.5	4C0		1.04	2.92		19.20
FAGU080	92204	25.9 27.4	1.5	1.4	4C0		1.05	2.65		17.14
FAGU080	92205	27.4 29.0	1.6	1.6	4A134		3.35	6.07		50.40
FAGU080	92206	29.0 30.5	1.5	1.4	4A134		3.30	8.49		56.57
FAGU080	92207	30.5 32.0	1.5	1.3	4A134		2.50	5.48		39.43
FAGU080	92208	32.0 33.5	1.5	1.3	4A13		1.45	1.65		22.29
FAGU080	92209	33.5 35.1	1.6	1.5	4A13		.15	1.18		9.94
FAGU080	92210	35.1 36.6	1.5	1.3	4A13		.35	1.40		13.03
FAGU080	92211	36.6 38.1	1.5	.7	4A13		1.14	1.95		22.29
FAGU080	92212	38.1 39.6	1.5	1.1	4A134		2.65	4.50		37.37
FAGU080	92213	39.6 41.1	1.5	1.3	4AE4		5.05	9.52		65.49
FAGU080	92214	41.1 42.7	1.6	1.4	4E4		3.45	5.15		52.46
FAGU080	92215	42.7 44.2	1.5	1.1	4E4		4.95	2.95		89.83
FAGU080	92216	44.2 45.7	1.5	1.5	4E4		4.40	8.98		65.49
FAGU080	92217	45.7 47.2	1.5	1.5	4C3		2.43	2.13		35.31
FAGU080	92218	47.2 48.8	1.6	1.6	4D3		5.65	4.30		71.66
FAGU080	92219	48.8 50.3	1.5	1.5	4AE4		2.33	3.80		32.23
FAGU080	92220	50.3 51.8	1.5	1.5	4AE4		1.45	3.78		26.40
FAGU080	92221	51.8 53.3	1.5	1.5	4AE4		5.35	5.20		72.69
FAGU080	92222	53.3 54.9	1.6	1.6	4AE4		2.78	4.90		39.43
FAGU080	92223	54.9 56.4	1.5	1.5	4AE4		3.05	6.70		50.40
FAGU080	92224	56.4 57.9	1.5	1.5	4AE4		3.00	6.98		39.43
FAGU080	92225	57.9 59.4	1.5	1.5	4AE0		1.00	2.53		20.23
FAGU080	92226	59.4 60.5	1.1	1.1	4AE4		3.43	7.80		55.54
FAGU078	92227	38.1 39.6	1.5	1.4	4A31		.25	1.20		17.14
FAGU078	92228	44.2 45.7	1.5	1.3	4A31		.05	1.00		9.94
FAGU078	92229	50.3 51.8	1.5	1.5	4A31		.05	.62		5.14
FAGU078	92230	56.1 57.6	1.5	1.5	4A10		.40	.42		26.40

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK UNIT	CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT
		FROM	TO								
FAGU078	92231	64.0	65.5	1.5	1.5	4A31		.05	.25		4.11
FAGU078	92232	70.1	71.6	1.5	1.5	4A31		.06	.37		9.94
FAGU078	92233	77.7	79.2	1.5	1.4	4A31		.14	.75		8.23
FAGU078	92234	83.8	85.3	1.5	1.5	4A31		.11	.55		18.17
FAGU078	92235	89.9	91.4	1.5	1.5	4A31		.09	.25		9.94
FAGU078	92236	94.9	96.5	1.6	1.2	4A31		1.73	2.20		28.46
FAGU078	92237	96.5	97.8	1.3	1.3	4A31		.66	1.28		20.23
FAGU078	92238	97.8	99.4	1.6	1.5	4A31		.13	.75		9.94
FAGA031	92239	114.6	115.9	1.3	1.3	4D34		4.95	7.05		68.60
FAGA031	92240	123.2	124.4	1.2	1.1	4C37		1.33	1.18		25.40
FAGA031	92241	133.6	134.4	.8	.3	4A0		1.68	1.62		20.20
FAGA031	92242	134.4	135.9	1.5	1.4	4A0		1.15	1.35		20.20
FAGA031	92243	148.3	148.8	.5	.4	4C07		.32	.98		6.20
FAGA031	92244	168.5	170.3	1.8	1.7	4E4		4.58	4.86		60.30
FAGA031	92245	170.3	171.9	1.6	1.4	4E4		3.90	3.60		44.20
FAGA031	92246	171.9	172.8	.9	.9	4E4		3.38	2.76		39.40
FAGA031	92247	172.8	174.0	1.2	1.1	4C3		.64	.34		15.10

TOTAL NUMBER OF ASSAYS 1758

> 90,000 ASSAYS - DRILL HOLE

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK UNIT	CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT
		FROM	TO								
4567506	92087	76.5	77.4	.9	.0	4C5	.02	.18	.21		
	92088	77.4	78.6	1.2	.0	4L14	.06	.43	.47		
	92089	78.6	79.9	1.3	.0	4L14	.04	.20	.29		
	92090	79.9	81.4	1.5	.0	4L14	.05	.87	.86		
	92091	98.8	101.8	3.0	.0	4LQ	.02	.01	.01		
	92092	101.8	105.5	3.7	.0	4LQ	.02	.01	.01		
	92093	105.5	108.8	3.3	.0	4LQ	.02		.01		
	92094	108.8	111.9	3.1	.0	4LQ	.02	.01	.01		
	92095	111.9	118.0	6.1	.0	4LQ	.02	.01	.01		
	92096	118.0	122.2	4.2	.0	4LQ	.02		.01		
	92097	122.2	126.2	4.0	.0	4LQ	.02		.01		
	92098	126.2	128.6	2.4	.0	4LQ	.02		.02		
	92099	135.0	138.1	3.1	.0	3G84	.03		.01		
	92100	138.1	141.1	3.0	.0	3G4L	.02	.02	.02		
92101	151.3	151.9	.6	.0	4CQ	.07	.02	.01			
92102	154.2	157.3	3.1	.0	3G8	.02	.02	.02			
4567507	92103	90.4	90.6	.2	.0	4A4#	.02	1.48	3.48		
	92104	90.6	91.4	.8	.0	4D5	.14	2.85	4.38		
	92105	91.4	91.6	.2	.0	4L13	.03	.03	.04		
	92106	91.6	92.4	.8	.0	4L13	.02		.02		
	92107	92.4	93.6	1.2	.0	4LD	.10	.56	.51		
	92108	93.6	94.2	.6	.0	4E4	.07	6.57	7.03		
	92109	94.2	94.6	.4	.0	4CQ	.08	.65	.42		
	92110	94.6	95.3	.7	.0	4L43	.02	.03	.04		
	92111	95.3	95.5	.2	.0	4DC	.10	.78	.63		
	92112	95.5	95.7	.2	.0	4DC	.03		.04		
	92113	95.7	96.9	1.2	.0	4DH	.13	2.03	3.24		
	92114	96.9	97.1	.2	.0	4CQ	.07	6.32	7.99		
	92115	97.1	98.0	.9	.0	4CQ	.15	.50	.33		
	92116	152.4	154.2	1.8	.0	3G8	.07	.02	.04		
	92117	154.2	154.7	.5	.0	5A19	.02	.18	.27		
	92118	154.7	154.8	.1	.0	4L13	.04	.02	.04		
	92119	154.8	155.3	.5	.0	4L13	.18	.06	.03		
92120	155.3	156.4	1.1	.0	3G84	.03	.02	.02			
92121	156.4	157.1	.7	.0	4L41	.12	.02	.01			
92122	157.1	157.9	.8	.0	4L41	.17	.01	.01			
92123	157.9	159.4	1.5	.0	4L41	.17		.01			
92124	159.4	161.0	1.6	.0	4LQ	.08	.01	.01			
92125	161.0	162.4	1.4	.0	4LQ	.02		.01			
4567509	92126	436.2	436.7	.5	.5	4A4	.07	1.90	4.08		
	92127	436.7	437.8	1.1	1.0	4AQ	.07	1.25	1.78		
	92128	438.4	439.5	1.1	1.0	4AQ	.02	.05	.07		
	92129	439.6	441.3	1.7	1.7	4AQ	.02	.14	.10		
	92130	441.9	443.0	1.1	1.0	4AQ	.02	.46	.60		
	92131	444.7	445.0	.3	.3	4E4	.34	3.15	11.10		
	92132	445.7	446.0	.3	.2	4H3	.04	1.50	1.78		
	92133	446.0	446.2	.2	.2	4AQ	.03	.35	.60		
	92134	446.2	446.5	.3	.3	4H3	.04	3.08	4.56		
	92135	447.8	448.0	.2	.2	4DC	.05	3.38	5.52		
	92136	448.0	449.3	1.3	1.3	4CQ	.08	1.01	1.02		
	92137	449.3	450.6	1.3	1.2	4CQ	.06	.53	.74		
	92138	450.6	452.5	1.9	1.8	4CQ	.06	.38	.72		
	92139	452.7	453.2	.5	.5	4CQ	.07	.43	.50		

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK UNIT	CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT
		FROM	TO								
4567509	92140	453.4	455.2	1.8	1.7	5B6	.03	.10	.07		
	92141	466.0	466.2	.2	.2	4C0	.03	1.03	1.66		
	92142	466.6	468.6	2.0	2.0	4L0	.03	.53	1.14		
	92143	468.6	469.6	1.0	.9	5B4	.06	.38	.25		
	92144	469.6	470.9	1.3	1.2	5B4	.05	.26	.39		
	92145	472.0	472.1	.1	.1	4D0	.08	1.73	5.59		
FAGA001	90000	262.5	263.3	.8	.0	5B21	.25	1.45	1.28	20.20	
FAGA004	90001	199.9	201.5	1.6	.0	4E4	.30	6.16	8.75		126.10
	90002	201.5	203.0	1.5	.0	4E4	.29	7.50	10.10		126.10
	90003	203.0	204.5	1.5	.0	4E4	.34	5.96	10.80		129.20
	90004	204.5	205.9	1.4	.0	4E4	.30	7.19	13.98		151.20
	90005	205.9	208.0	2.1	.0	4L0	.16	2.23	3.84		60.30
	90308	146.8	149.8	3.0	.0	5B46	.04	.10	.16		2.10
90309	157.0	160.6	3.6	.0	5B2	.08	.30	.25		4.10	
FAGA005	90006	160.5	161.7	1.2	.0	4E4	.25	6.50	21.50		113.80
	90007	161.7	163.7	2.0	.0	4E4	.16	4.70	22.90		59.00
	90008	163.7	165.4	1.7	.0	4E4	.32	9.20	15.50		176.20
	90009	165.4	166.0	.6	.0	4E4	.06	.38	.38		9.60
	90010	166.0	166.5	.5	.0	4E4	.05	3.98	8.06		61.00
	90011	166.5	169.6	3.1	.0	5B2	.06	.38	.62		2.70
	90012	169.6	170.5	.9	.0	4E4	.19	4.05	6.85		77.50
	90013	170.5	171.8	1.3	.0	4E4	.16	6.45	12.30		104.90
	90014	171.8	173.1	1.3	.0	4E4	.28	6.60	13.10		152.20
	90015	173.1	174.3	1.2	.0	4E4	.29	5.78	9.24		149.50
	90016	174.3	175.9	1.6	.0	4E4	.33	5.85	9.03		82.30
	90017	175.9	177.1	1.2	.0	4E4	.34	6.90	9.10		142.60
	90018	177.1	178.8	1.7	.0	4E4	.18	9.20	17.40		125.50
	90019	178.8	180.4	1.6	.0	4AC	.05	1.13	2.28		16.50
90310	155.9	159.0	3.1	.0	5B26	.04	.20	.31		.21	
FAGA008	90521	72.7	74.7	2.0	.0	4A0		.98	1.12	13.70	
	90522	74.7	76.2	1.5	.0	4AC		.90	1.26	16.50	
	90523	76.2	80.2	4.0	.0	4A0		.80	.90	11.00	
	90524	80.2	81.4	1.2	.0	4AC		.21	.08	2.70	
	90525	93.5	95.1	1.6	.0	4D5		2.03	4.08	37.00	
	90526	95.1	95.3	.2	.0	4D5		2.03	4.08	37.00	
	90527	95.3	96.9	1.6	.0	4D5		2.48	4.62	31.50	
	90528	96.9	98.1	1.2	.0	4D5		3.08	6.48	39.80	
	90529	177.9	180.6	2.7	.0	4D5		3.23	6.11	50.70	
FAGA009	90020	113.9	115.5	1.6	.0	4AL	.09	1.18	3.36		21.90
	90021	115.5	117.0	1.5	.0	4L4	.03	.95	2.28		11.00
	90022	117.0	118.5	1.5	.0	4A4	.03	2.23	5.28		62.40
	90023	118.5	120.0	1.5	.0	4A4	.04	2.50	5.40		57.30
	90024	120.0	121.6	1.6	.0	4LA	.05	2.03	4.20		38.40
	90025	121.6	123.1	1.5	.0	4L1	.03	.98	1.40		19.20
	90026	123.1	124.6	1.5	.0	4L1	.06	2.00	4.02		27.40
	90027	132.3	133.8	1.5	.0	4A14	.08	2.85	6.12	57.60	
	90028	133.8	135.3	1.5	.0	4A14	.12	5.55	10.52	96.00	
	90029	135.3	136.9	1.6	.0	4A14	.09	7.50	10.63	95.30	
	90030	136.9	138.4	1.5	.0	4A14	.10	7.35	11.88	103.20	
90031	138.4	139.9	1.5	.0	4A14	.05	2.45	5.16	74.70		

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK UNIT	CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT
		FROM	TO								
FAGA009	90032	139.9	141.5	1.6	.0	4A14	.04	1.90	4.26	55.50	
FAGA011	90342	123.9	127.7	3.8	.0	4L0	.21	1.95	1.26		38.40
	90343	135.9	138.2	2.3	.0	4LH	.03	.28	.27		7.50
	90344	150.4	152.4	2.0	.0	4EL4	.15	4.88	3.84		32.90
	90345	152.4	154.2	1.8	.0	4EL4	.20	4.20	3.90		26.70
	90346	178.0	180.3	2.3	.0	4GE4	.15	6.00	9.40		112.40
	90347	180.2	182.6	2.4	.0	4G4	.20	8.74	13.50		156.30
FAGA012	90534	247.2	250.2	3.0	.0	4C5	.04	2.00	2.70	30.90	
	90536	250.2	253.3	3.1	.0	4D5	.07	3.45	3.06	44.60	
	90537	253.3	256.3	3.0	.0	4D5	.05	2.35	3.48	38.40	
FAGA013	90117	44.0	48.3	4.3	4.3	4G4	.16	8.10	8.40		107.00
	90118	48.3	52.3	4.0	4.0	4G4	.19	7.65	5.52		92.60
	90119	54.9	59.0	4.1	4.1	4EG	.21	5.03	4.20		91.90
	90120	59.0	60.1	1.1	1.1	4E0	.15	1.50	1.90		29.50
	90121	60.1	61.6	1.5	1.5	4E4	.20	5.25	5.40		71.30
	90122	61.6	64.2	2.6	2.6	4KC	.08	1.25	.16		33.90
	90123	64.2	66.8	2.6	2.6	4K0	.20	1.63	.90		53.50
	90124	121.3	123.1	1.8	1.8	5AG	.03	.90	2.00		24.70
FAGA014	90033	192.6	193.2	.6	.0	4L24	.19	1.45	1.22	21.90	
	90034	266.4	269.1	2.7	.0	4A0	.16	.29	.42		31.50
	90035	269.1	273.1	4.0	.0	4A0	.16	.63	.69		37.00
	90036	273.1	275.8	2.7	.0	4EG4	.30	6.53	6.96		91.50
	90037	275.8	278.9	3.1	.0	4A0	.20	.55	.66		12.30
	90038	278.9	281.9	3.0	.0	4A0	.17	2.00	2.76		53.50
	90039	281.9	283.5	1.6	.0	4A0	.15	.33	.46		21.90
	90040	283.5	287.1	3.6	.0	4EG	.20	1.73	2.00		32.90
FAGA017	90125	232.0	235.0	3.0	3.0	4E71	.30	2.00	1.58		34.30
	90126	235.0	237.1	2.1	2.1	4E71	.22	.30	.30		11.00
	90127	237.1	239.0	1.9	1.9	4G4	.23	6.38	7.92		87.80
FAGA019	90179	102.4	103.8	1.4	1.4	4C0	.22	1.85	1.92		47.30
	90180	103.8	105.3	1.5	1.5	4C0	.13	1.18	1.02		11.00
	90181	105.3	108.2	2.9	2.9	4CG4	.11	6.68	5.64		109.00
	90182	134.7	135.9	1.2	1.2	5AD	.02	.05	.17		1.40
	90183	137.8	139.6	1.8	1.8	4A13	.17	1.15	2.00	31.50	
	90184	139.6	142.4	2.8	2.8	4EG	.34	.38	.60	21.90	
	90185	142.4	145.5	3.1	3.0	4EG4	.07	7.35	9.36		139.90
	90186	145.5	147.8	2.3	2.3	4C0	.18	.25	.82		14.40
	90187	147.8	150.3	2.5	2.5	4C0	.14	2.28	1.60		34.30
	90188	150.3	152.4	2.1	2.1	4A13	.06	4.95	6.96		60.30
	90189	161.9	163.7	1.8	.3	4L14	.11	2.25	4.68		58.30
	90190	163.7	164.6	.9	.5	4E4	.23	4.35	6.84		56.20
	90191	164.6	165.5	.9	.8	4E4	.21	7.55	12.72		111.80
	90192	165.5	166.7	1.2	1.2	4E4	.11	3.15	4.74		50.10
	90193	166.7	168.2	1.5	1.2	4E4	.11	2.05	3.72		38.40
	90194	168.2	169.8	1.6	1.6	4E4	.10	2.28	3.90		53.50
	90195	169.8	171.3	1.5	1.5	4E4	.10	2.50	6.24		52.10
	90196	171.3	172.8	1.5	1.5	4E4	.18	4.50	9.48		76.80
	90197	172.8	174.4	1.6	1.6	4E4	.25	4.74	8.64		76.80
	90198	174.4	175.9	1.5	1.5	4E4	.17	5.78	10.20		109.70

DDH	SAMPLE	----DEPTHS----		INT	REC	ROCK UNIT	CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT
		FROM	TO								
FAGA019	90199	175.9	176.7	.8	.8	4E4	.05	3.08	5.76		67.90
	90200	176.7	177.8	1.1	1.1	4L14	.03	1.85	3.33		46.60
	90201	194.2	197.2	3.0	2.9	4D45	.20	9.15	15.36		137.80
	90202	197.2	198.4	1.2	1.2	4E1	.29	1.90	2.88		27.40
	90203	198.4	200.9	2.5	2.5	4E14	.26	5.70	9.49		90.50
	90204	200.9	202.5	1.6	1.6	4E14	.33	2.70	3.30		50.70
	90205	202.5	205.3	2.8	2.8	4E14	.29	2.93	4.14		55.90
	90206	207.6	208.4	.8	.8	4A13	.42	.08	.37	16.50	
FAGA020	90538	183.8	185.0	1.2	1.2	5D4*	.04	.43	.70	11.00	
	90539	185.0	186.8	1.8	1.8	4A4	.10	2.48	4.14	41.80	
	90540	188.1	189.6	1.5	1.5	4AC	.04	1.73	3.06	28.10	
	90541	189.6	191.1	1.5	1.5	4A4	.08	3.38	2.46	43.20	
	90542	191.1	192.6	1.5	1.5	4A4	.04	2.50	3.54	56.20	
	90543	192.6	194.2	1.6	1.5	4A4	.06	2.85	5.52	35.70	
	90544	202.5	204.8	2.3	2.3	4A4	.14	2.42	3.16	37.90	
	90545	204.8	206.0	1.2	1.2	4A4	.04	5.25	8.04	78.20	
	90546	215.5	217.3	1.8	1.8	4A4	.23	4.79	6.68	87.80	
	90547	217.3	218.8	1.5	1.5	4A4	.04	3.38	7.44	66.50	
	90548	218.8	220.4	1.6	1.5	4A4	.06	2.85	6.72	50.10	
	90549	220.4	221.9	1.5	1.5	4A4	.05	3.15	7.44	55.50	
	90550	221.9	223.4	1.5	1.5	4A4	.04	2.43	5.40	45.90	
	90551	223.4	224.9	1.5	1.5	4A4	.06	2.00	3.72	37.70	
	90552	224.9	226.5	1.6	1.5	4A0	.06	.58	1.18	19.20	
	91354	325.0	328.0	3.0	3.0	4CA0		1.13	1.04	16.10	
	91355	332.5	333.5	1.0	.8	4GE4		4.43	6.21	77.80	
	91356	337.7	338.5	.8	.8	4GA		2.08	2.28	53.50	
	91357	338.5	340.2	1.7	1.7	4GA		1.63	2.88	32.20	
	91358	343.2	344.8	1.6	1.6	4EG		3.38	5.55	67.50	
	91359	351.0	352.0	1.0	1.0	4E4		2.78	2.46	45.30	
	91360	352.0	353.0	1.0	1.0	4E4		3.00	2.94	35.30	
	91361	355.0	356.7	1.7	1.7	4G4		5.03	6.66	78.80	
	91362	360.6	361.6	1.0	1.0	4CE4		3.15	6.33	47.30	
	91363	362.7	363.9	1.2	1.2	4E4		4.43	7.94	63.40	
	91364	363.9	364.7	.8	.8	4E4		2.20	3.18	40.40	
91365	364.7	366.0	1.3	1.3	4C0		1.03	1.94	25.40		
91366	366.0	367.0	1.0	1.0	4C3		1.40	2.22	30.20		
91367	367.0	368.0	1.0	1.0	4C3		1.70	2.94	34.30		
91368	368.0	369.0	1.0	1.0	4C0		1.50	1.60	30.20		
91369	370.0	371.0	1.0	1.0	4D0		3.75	4.32	64.50		
91370	371.0	372.2	1.2	1.2	4H4		3.90	4.02	60.30		
91371	372.2	372.6	.4	.4	4HC		1.90	1.84	46.30		
91372	372.6	374.7	2.1	2.1	4EC		1.75	2.70	32.20		
91373	257.0	258.5	1.5	1.5	5B9	.05	.98	1.74	24.70		
FAGA021	90090	100.1	101.1	1.0	.9	5B20	.02	.03	.10		
	90091	101.1	103.5	2.4	2.0	4E4	.08	5.78	11.35		79.50
	90092	103.5	104.3	.8	.7	5D4*	.02	.10	.30		
	90093	104.3	107.1	2.8	2.1	4AE4	.15	8.25	14.83		149.50
	90094	107.1	109.4	2.3	1.8	4AL	.03	2.23	4.26		32.20
	90095	109.4	112.4	3.0	1.9	4A4	.06	4.43	8.76		56.20
	90096	112.4	113.7	1.3	1.3	4LA4	.06	3.75	1.44		39.80
	90097	113.7	115.2	1.5	1.4	4A4	.05	4.20	1.50		45.90
	90098	115.2	117.4	2.2	2.2	4AC	.08	.68	1.74		9.60
	90099	117.4	119.1	1.7	1.7	4AC	.08	.64	1.66		9.60

DDH	SAMPLE	----DEPTHS----		INT	REC	ROCK UNIT	CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT
		FROM	TO								
FAGA021	90100	119.1	121.1	2.0	2.0	4L34	.10	.70	1.34		11.00
	90101	121.1	123.2	2.1	1.7	4L34	.08	.63	1.14		10.30
	90102	132.3	133.8	1.5	1.5	5B6	.02	.03	.05		
	90103	167.0	168.6	1.6	1.4	5B26	.02	.08	.33		
	90104	179.8	181.2	1.4	1.4	4LC	.03	.08	.10		8.90
	90105	181.2	183.3	2.1	2.0	4EA4	.12	2.43	4.74		42.50
	90106	183.3	185.3	2.0	1.7	4E4	.09	3.08	5.04		48.00
	90107	185.3	186.8	1.5	1.5	4E4	.09	2.50	4.20		52.10
	90108	186.8	189.9	3.1	3.1	4E4	.12	4.43	8.76		71.30
	90109	189.9	192.9	3.0	3.0	4EG4	.04	4.28	9.12		76.80
	90110	192.9	194.5	1.6	1.6	4EG4	.17	5.03	9.36		83.60
	90111	194.5	196.0	1.5	1.5	4E4	.17	6.83	11.50		128.90
	90112	196.0	197.5	1.5	1.5	4E4	.15	2.25	4.26		51.40
	90175	197.5	198.7	1.2	1.2	4A4	.12	5.18	9.00		45.30
FAGA022	90553	154.2	154.7	.5	.5	4E80	.44	1.45	1.58	23.30	
	90554	181.0	183.2	2.2	2.2	4E4	.13	5.03	5.52	68.60	
	90555	183.2	184.8	1.6	1.5	4DL	.16	6.00	6.84	105.90	
	90556	184.8	186.9	2.1	2.1	4L41	.13	.78	1.06	9.90	
	90557	186.9	188.7	1.8	1.8	4H2S	.24	.85	2.40	30.20	
	90558	229.9	231.0	1.1	1.1	4E4	.12	4.35	8.50	59.00	
	90559	231.0	232.1	1.1	.7	4E4	.27	6.83	8.40	133.00	
	90560	232.1	233.8	1.7	.9	4E4	.15	3.23	4.44	50.70	
	90561	233.8	236.8	3.0	.3	4A4	.09	5.33	8.88	78.20	
	90562	236.8	239.9	3.1	.3	4A4	.07	2.35	5.16	48.00	
	90563	239.9	242.6	2.7	2.7	4A4	.06	2.08	4.56	59.00	
	90564	242.6	243.4	.8	.2	4L12	.08	1.93	3.06	23.30	
	90565	243.4	245.8	2.4	2.4	4L12	.08	.23	.43	5.50	
	90566	245.8	247.0	1.2	1.2	4A0	.12	.63	.25	20.60	
	90567	247.0	250.0	3.0	3.0	4A4	.10	3.83	6.96	52.10	
	90568	250.0	251.3	1.3	1.3	4E0	.28	.69	1.40	16.50	
	90569	251.3	252.6	1.3	1.2	4E0	.31	2.08	2.00	45.30	
	90570	252.6	254.5	1.9	1.9	4A4	.12	4.35	8.16	62.40	
	90571	254.5	257.4	2.9	2.9	4E4	.21	4.35	7.68	66.50	
	90572	270.0	270.5	.5	.5	4G4	.08	6.68	11.45	152.20	
	90573	274.4	275.3	.9	.9	4A0	.04	1.58	3.00	27.40	
	90574	275.3	276.8	1.5	1.5	4D4	.08	6.60	12.67	94.60	
	90575	276.8	278.8	2.0	2.0	4D4	.15	6.00	11.92	127.50	
	90576	342.9	344.9	2.0	2.0	4EG4	.10	4.35	7.20	80.90	
90577	344.9	345.4	.5	.3	4E4	.09	6.08	10.65	98.70		
90578	345.4	347.5	2.1	1.8	4A43	.04	3.53	6.36	43.90		
90579	347.5	349.2	1.7	1.6	4A43	.04	3.53	6.60	49.40		
90580	349.2	352.2	3.0	.3	4G4	.10	4.88	7.80	100.10		
90581	352.2	354.8	2.6	2.6	4G4		5.18	8.76	88.80		
90582	354.8	355.5	.7	.6	5C4*		.50	.77	6.20		
90583	355.5	356.3	.8	.8	4G4		4.58	7.80	87.80		
90584	356.3	356.7	.4	.3	4G0		2.55	3.54	33.30		
90585	361.1	362.3	1.2	1.2	4GL		3.08	5.28	64.50		
90586	362.3	363.3	1.0	.7	5B62		.14	.12	1.00		
90979	356.7	357.5	.8	.8	4L2		.47	.40	8.20		
FAGA023	90134	221.9	224.3	2.4	.0	4L0		.03	.03		2.10
	90135	245.2	246.9	1.7	.0	4L0		.32	.76		5.10
	91074	78.0	79.9	1.9	.0	4E4	.12	13.00	20.80	164.00	
	91075	79.9	83.1	3.2	.0	4E4	.22	6.47	12.70	101.00	

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK UNIT	CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT
		FROM	TO								
FAGA023	91076	83.1	84.9	1.8	.0	4AC	.11	1.83	2.25	33.00	
	91077	84.9	86.7	1.8	.0	4A4	.06	2.67	4.50	37.00	
FAGA024	90269	139.8	142.8	3.0	.0	4G4	.13	6.15	5.40		90.80
	90270	142.8	143.4	.6	.0	4DE	.17	1.25	.74		20.20
	90271	143.4	144.7	1.3	.0	4EL	.03	.07	.08		
	90272	144.7	146.0	1.3	.0	4E4	.15	5.55	3.54		86.70
	90273	146.0	147.4	1.4	.0	4L5	.03	.18	.04		4.10
	90274	147.4	150.4	3.0	.0	4D4	.18	7.20	6.12		97.70
	90275	150.4	150.9	.5	.0	4L0	.04	.65	.68		9.30
	90276	177.4	177.9	.5	.0	5A3	.03	.78	1.50		3.10
	90277	177.9	178.6	.7	.0	5A3	.03	.08	.11		2.10
	90278	180.1	182.0	1.9	.0	4A4	.10	2.13	3.72		35.30
	90279	182.0	185.0	3.0	.0	4A4	.12	7.20	10.20		102.80
	90280	185.0	187.3	2.3	.0	4A4	.20	3.83	7.56		75.80
	90281	187.3	188.4	1.1	.0	4A4	.04	2.40	4.50		37.40
	90282	188.4	189.1	.7	.0	4A0	.04	.85	1.74		16.10
	90283	189.1	191.9	2.8	.0	5D4	.05	.19	.50		5.10
	90284	191.9	194.2	2.3	.0	4A4	.13	8.25	14.63		111.10
	90285	194.2	196.1	1.9	.0	4A4	.21	4.13	7.92		64.50
	90286	196.1	197.6	1.5	.0	4A4	.10	3.83	6.96		60.30
	90287	197.6	199.4	1.8	.0	4A4	.15	2.35	5.64		37.40
	90288	199.4	201.0	1.6	.0	4A4	.05	2.85	4.92		39.40
	90289	201.0	203.1	2.1	.0	4A4	.08	5.70	6.24		60.30
	90290	203.1	204.2	1.1	.0	4A4	.15	4.05	2.76		57.60
	90291	218.5	219.4	.9	.0	4A0	.07	1.65	2.34	15.10	
	90292	219.4	221.3	1.9	.0	4A4	.15	2.05	3.18	31.20	
	90293	221.3	223.1	1.8	.0	4A4	.12	2.50	3.54	32.20	
	90294	223.1	223.4	.3	.0	4E4	.10	2.50	3.24	42.50	
	90295	223.4	224.6	1.2	.0	4A0	.06	.72	.98		15.10
	90296	224.6	226.2	1.6	.0	5A1	.03	.03	1.06		1.00
	90297	226.2	226.6	.4	.0	5A1	.02	.25	.41		3.10
	90298	226.6	228.0	1.4	.0	4L0	.50	.37	1.60		9.90
	90299	228.0	228.9	.9	.0	4L0	.50	2.15	3.90		60.30
	90300	228.9	229.5	.6	.0	4L0	.50	2.50	4.92		70.60
	90301	229.5	229.8	.3	.0	4L0	.50	.08	.34		3.10
90302	229.8	231.0	1.2	.0	4C0	.50	4.65	8.52		96.70	
90303	231.0	233.8	2.8	.0	5A3	.50	.13	.19		4.10	
90304	249.6	251.8	2.2	.0	5A3	.50	.05	.11		2.10	
90305	253.5	254.9	1.4	.0	5A1	.50	.05	.10		1.00	
90306	254.9	257.3	2.4	.0	0QC	.50	1.28	2.28		35.30	
90307	343.6	345.2	1.6	.0	5B6	.50	.08	.13		2.10	
FAGA026	91081	46.6	49.7	3.1	1.1	4D5		1.55	3.84		25.40
	91082	49.7	51.5	1.8	1.8	4D5		2.30	5.16		28.50
	91083	55.8	57.8	2.0	2.0	4D5		2.00	3.24		20.20
	91084	57.8	59.4	1.6	1.6	4E4		4.13	9.96		100.80
	91085	59.4	61.4	2.0	2.0	4E4		5.55	13.20		103.90
	91086	62.1	63.7	1.6	1.6	4E4		6.30	14.45		102.80
	91087	63.7	65.2	1.5	.0	4E4		6.30	14.45		102.80
	91088	65.2	68.0	2.8	2.8	4E4		7.35	15.54		116.90
	91089	68.0	69.6	1.6	1.6	4E4		3.30	11.67		51.40
	91090	70.4	71.2	.8	.8	4LE		3.15	6.24	51.40	
	91091	71.2	72.5	1.3	1.3	4LE		.53	1.44	9.90	
91092	72.5	73.7	1.2	1.1	4LE		3.68	8.04	63.40		

DDH	SAMPLE	----DEPTHS----	INT	REC	ROCK UNIT	CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT
		FROM TO								
FAGA026	91093	73.7 74.5	.8	.0	4LE		6.60	16.30	105.90	
	91094	96.5 98.3	1.8	1.8	4A13		1.58	1.06	22.30	
	91095	98.3 100.6	2.3	2.2	4A134		3.08	3.72	35.30	
	91096	100.6 103.3	2.7	2.6	4A13		.32	.74	6.20	
	91097	103.3 105.0	1.7	1.5	4A13		1.38	1.35	17.10	
	91098	105.0 106.2	1.2	1.2	4A134		7.05	8.04	97.70	
	91099	106.2 109.0	2.8	2.6	4A13		1.35	3.00	20.20	
	92000	128.5 129.5	1.0	1.0	4A4		3.98	4.20	64.50	
	92001	129.5 131.8	2.3	2.0	4A0		1.50	1.43		28.50
	92002	131.8 134.7	2.9	2.9	4E1		2.33	2.40		41.50
	92003	134.7 137.8	3.1	3.1	4E14		4.73	4.02		65.50
	92004	137.8 140.8	3.0	3.0	4E14		3.08	2.88		48.30
	92005	140.8 143.9	3.1	3.1	4E1		1.33	2.28		27.40
	92006	143.9 144.8	.9	.9	4E14		3.00	3.54		46.30
	92007	144.8 147.1	2.3	.6	4E14		2.08	3.48		35.30
	92008	208.7 209.5	.8	.0	4D4		4.95	6.84	80.60	
	92009	210.4 211.7	1.3	.0	4D4		4.13	5.52	73.70	
FAGA027	91000	160.3 160.9	.6	.5	4A0		1.90	2.82		35.30
	91001	160.9 162.0	1.1	.9	4A4		2.50	4.50		48.30
	91002	162.0 165.2	3.2	3.2	4A4		2.23	4.92		45.30
	91003	165.2 168.2	3.0	3.0	4A4		2.78	4.92		47.30
	91004	168.2 169.8	1.6	1.5	4A4		3.45	5.64		82.60
	91005	169.8 172.1	2.3	2.3	4A0		1.63	3.24		26.40
	91006	172.1 175.0	2.9	2.9	4C0		.93	.77		11.00
	91007	175.0 177.7	2.7	2.6	4C0		1.14	.89		16.10
	91008	177.7 180.7	3.0	3.0	4C0		2.00	2.10		26.40
	91009	180.7 183.3	2.6	2.4	4C0		3.08	.88		33.30
	91010	183.3 184.5	1.2	1.2	4D0		2.78	3.60		32.20
	91011	209.9 212.1	2.2	2.2	4D0		2.35	3.86		35.30
	91012	212.1 215.2	3.1	3.0	4C0		2.40	2.28		35.30
	91013	215.2 217.3	2.1	2.1	4D0		4.13	3.18		55.50
	91014	217.3 219.2	1.9	1.8	4A4		5.10	3.24		68.60
	91015	219.2 221.0	1.8	1.8	4A4		5.25	6.48		75.80
	91016	221.0 223.0	2.0	2.0	4A4		7.05	10.98		119.00
	91017	223.0 225.2	2.2	2.2	4A4		2.50	3.24		44.20
	91018	225.2 228.3	3.1	3.0	4C0		1.05	2.22		18.20
91019	228.3 231.3	3.0	3.0	4C0		2.70	3.42		37.40	
91020	231.3 234.4	3.1	3.0	4C0		1.23	1.06		18.20	
91021	325.6 326.3	.7	.7	4L0		.07	.16		1.00	
FAGA028	92010	50.6 51.1	.5	.4	5D0		.84	.84		15.10
	92011	242.3 244.0	1.7	1.7	4L15		.12	.09		5.10
	92012	248.7 250.2	1.5	1.5	4L1		.05	.08		1.00
FAGA029	92033	368.5 371.2	2.7	2.5	4AH		.93	2.22	9.94	
	92034	371.2 374.2	3.0	3.0	4A0		1.23	2.22	18.16	
	92035	374.2 375.3	1.1	1.0	5C\$		.65	1.28	7.20	
	92036	375.3 377.6	2.3	2.3	4A0		1.65	2.58	14.05	
	92037	377.6 379.1	1.5	1.2	4C5		.80	1.42	9.94	
	92038	379.1 382.2	3.1	3.1	4AC		1.18	1.46	15.00	
	92039	385.7 388.6	2.9	2.8	4A0		1.44	2.40	24.34	
	92040	388.6 391.6	3.0	3.0	4A0		1.23	2.00	16.11	
	92041	391.6 393.9	2.3	2.2	4AD		2.00	4.00	17.14	
	92042	403.6 405.0	1.4	1.3	4C0		1.28	2.94	22.28	

DDH	SAMPLE	---DEPTHS---	INT	REC	ROCK	CU	PB	ZN	AG(AA)	AG(FA)
		FROM TO			UNIT	%	%	%	G/MT	G/MT
FAGA029	92043	406.6 407.9	1.3	1.0	4A4		1.80	4.20	37.37	
	92044	407.9 408.4	.5	.4	4A4		2.28	4.92	44.22	
	92045	408.4 409.9	1.5	1.0	4A4		2.50	4.80	42.51	
	92046	409.9 411.4	1.5	1.5	4A4		1.93	4.20	32.22	
	92047	411.4 413.3	1.9	.3	4A0		2.48	1.36	30.17	
	92048	413.3 414.5	1.2	1.2	4A4		2.33	5.10	30.17	
	92049	436.0 436.8	.8	.7	5A6		.22	.41	5.14	
	92050	436.8 438.6	1.8	1.7	4AE		3.68	16.67	80.56	
	92051	438.6 439.0	.4	.4	4A4		1.35	5.40	21.25	
	92052	439.0 439.8	.8	.7	4A4		1.30	3.84	22.28	
	92053	441.9 442.9	1.0	.9	5A6		.58	1.60	12.00	
FAGA031	92239	114.6 115.9	1.3	1.3	4D34		4.95	7.05		68.60
	92240	123.2 124.4	1.2	1.1	4C37		1.33	1.18		25.40
	92241	133.6 134.4	.8	.3	4A0		1.68	1.62		20.20
	92242	134.4 135.9	1.5	1.4	4A0		1.15	1.35		20.20
	92243	148.3 148.8	.5	.4	4C07		.32	.98		6.20
	92244	168.5 170.3	1.8	1.7	4E4		4.58	4.86		60.30
	92245	170.3 171.9	1.6	1.4	4E4		3.90	3.60		44.20
	92246	171.9 172.8	.9	.9	4E4		3.38	2.76		39.40
	92247	172.8 174.0	1.2	1.1	4C3		.64	.34		15.10
FAGA035	90260	325.6 327.2	1.6	.0	5A9		.13	.06		5.10
	90261	328.0 328.6	.6	.6	5A9		1.10	1.18		23.30
FAGA045	90160	50.9 51.8	.9	.9	4B0		.73	3.18	9.90	
	90162	66.4 67.2	.8	.6	10Q0		2.30	4.42	19.20	
	90163	177.7 178.8	1.1	.9	5D4*		1.48	.86	19.20	
FAGA052	90164	78.0 78.3	.3	.2	5B69		11.00	20.45	171.40	
	90165	85.0 85.9	.9	.6	5B69		1.75	2.22	27.40	
	90166	86.1 87.6	1.5	.0	4DGL		8.18	10.72	110.00	
	91072	143.9 146.9	3.0	2.8	4A0		.25	.55	7.20	
	91073	146.9 149.0	2.1	2.1	4A0		.18	.44	7.20	
FAGA055	90136	174.7 175.2	.5	.0	5B6		1.08	2.76		17.10
FAGA056	90215	104.0 106.1	2.1	.2	F		1.98	3.54	30.20	
	90216	185.5 186.0	.5	.5	4L04		1.08	1.80	15.10	
FAGA058	92013	157.0 157.9	.9	.8	5C4*		.03	.13		2.10
	92014	159.7 160.6	.9	.2	4LC		.15	.03		5.10
	92015	160.6 164.0	3.4	.1	4LC		.22	.46		4.10
	92016	164.0 165.8	1.8	1.4	4L0		.18	.25		1.00
FAGA059	91298	258.7 260.5	1.8	1.8	4EA		5.93	11.11	90.80	
	91299	260.5 262.1	1.6	1.6	4A4		2.10	4.20	37.40	
	91300	262.1 265.2	3.1	3.1	4A0		1.28	2.52	22.30	
	91301	265.2 268.2	3.0	3.0	4AC		1.88	3.96	30.20	
	91302	268.2 268.9	.7	.7	4C5		1.38	1.38	19.20	
	91303	269.8 271.7	1.9	1.9	4AC		1.65	3.18	25.40	
	91304	271.7 273.5	1.8	1.8	4D5		2.40	4.02	34.30	
	91305	273.5 274.3	.8	.8	4C5		1.23	2.34	17.10	
	91306	280.1 283.3	3.2	3.2	5A19		.15	.28	3.10	
	91307	283.3 284.0	.7	.7	5A19		.85	1.36	13.00	

DDH	SAMPLE	---DEPTHS---	INT	REC	ROCK UNIT	CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT
		FROM TO								
FAGA059	91308	284.5 285.3	.8	.8	4AG		.73	1.24	12.00	
	91309	285.6 287.2	1.6	1.5	4AG		1.03	1.98	14.10	
	91310	287.2 288.6	1.4	1.4	4AG		.66	1.60	8.20	
	91311	288.6 290.3	1.7	1.7	4C5		.30	.44	4.10	
	91312	308.5 310.4	1.9	1.9	4AG		.49	.94	7.20	
	91313	310.4 312.8	2.4	2.2	4AC		.44	1.00	7.20	
	91314	312.8 315.0	2.2	2.2	4C5		1.38	2.34	21.30	
	91315	315.0 316.2	1.2	1.2	4CQ		.65	.95	9.90	
	91316	316.2 318.8	2.6	2.6	4CQ		.65	1.24	9.90	
	91317	318.8 321.9	3.1	2.8	4CQ		.65	1.14	9.90	
	91318	321.9 323.4	1.5	1.2	4AG		.63	.56	6.20	
	91319	323.4 324.7	1.3	1.3	3C4\$		.07	.09	1.00	
	91320	324.7 327.1	2.4	2.1	4A4		3.53	6.12	46.30	
	91321	327.1 327.8	.7	.7	4A30		1.28	1.40	17.10	
	91322	327.8 329.7	1.9	1.9	4A30		.90	.45	20.20	
	91323	329.7 331.6	1.9	1.9	4DG		6.15	10.38	100.80	
	91324	331.6 333.4	1.8	1.8	4G4		4.95	8.52	90.80	
	91325	333.4 335.4	2.0	2.0	4E4		8.43	14.39	104.90	
	91326	335.4 336.9	1.5	1.2	4E#4		5.70	11.67	121.00	
	91327	336.9 337.5	.6	.6	3C4\$		1.45	2.40	23.30	
	91328	337.5 337.8	.3	.3	3C4\$		.14	.72	6.20	
	91329	337.8 340.0	2.2	.9	5A6\$		.19	.38	2.10	
	91330	340.0 340.3	.3	.3	4E4\$		9.65	16.21	201.60	
	91331	340.3 341.0	.7	.5	3G4		.05	.18	6.20	
	91332	341.0 341.4	.4	.4	4E46		14.61	19.44	196.80	
	91333	341.4 343.1	1.7	1.7	5A6\$		.07	.12	2.10	
	91334	343.1 344.5	1.4	1.2	4E46\$		11.00	17.19	176.50	
	91335	380.5 381.7	1.2	1.2	4AC		2.33	2.52	53.10	
	91336	381.7 382.9	1.2	1.1	4G0		3.00	4.62	68.60	
	91337	384.1 384.4	.3	.3	4G4		4.50	8.16	43.50	
	91338	384.7 387.2	2.5	2.5	4G4		5.10	8.28	73.70	
	91339	387.2 387.6	.4	.4	4L4\$		.68	.40	8.20	
	91340	387.6 389.8	2.2	2.2	4G4		6.30	9.41	100.80	
	91341	389.8 390.9	1.1	1.1	4G4		5.70	8.52	100.80	
	91342	390.9 392.4	1.5	1.4	4G4		5.70	8.64	80.60	
	91343	392.4 393.6	1.2	1.2	4L12		2.10	1.84	44.20	
FAGA060	90113	116.3 116.6	.3	.3	4LQ		.68	.51	19.20	
	90114	259.7 262.1	2.4	2.1	5B6		.07	.04		
	90115	339.7 340.2	.5	.5	5B26		1.63	.66		27.40
FAGA061	91344	240.5 242.2	1.7	1.6	5A6\$		.39	.72	6.20	
	91345	242.2 243.2	1.0	1.0	5A6\$		1.40	2.46	17.10	
	91346	243.2 244.1	.9	.8	4E14		1.93	4.02	40.40	
	91347	244.1 245.3	1.2	1.1	5C4\$		1.05	1.66	11.00	
	91348	256.0 257.6	1.6	1.4	4Q43		1.88	2.64	35.30	
	91349	264.1 265.8	1.7	1.7	4CQ		1.55	1.88	22.30	
	91350	265.8 268.6	2.8	2.8	4AG		1.85	3.00	32.60	
	91351	268.6 271.6	3.0	3.0	4AC		1.50	1.72	22.30	
	91352	271.6 273.5	1.9	1.9	4AC		1.28	1.76	19.20	
	91353	273.5 276.4	2.9	2.9	4AC		1.10	1.54	15.10	
FAGA062	90227	166.0 167.0	1.0	.0	4L4		1.12	1.14		12.00
FAGA064	92054	320.8 322.1	1.3	1.3	4QAC		.85	1.68	7.20	

DDH	SAMPLE	----DEPTHS----		INT	REC	ROCK UNIT	CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT
		FROM	TO								
FAGA064	92055	322.8	324.9	2.1	2.0	4A0		1.13	1.80	15.08	
	92056	369.1	372.1	3.0	.6	4L74		1.10	2.34	15.08	
	92057	385.6	387.0	1.4	1.4	4A0		1.43	2.58	15.08	
	92058	387.0	389.2	2.2	2.1	4A0		1.33	2.40	15.08	
	92059	390.9	392.7	1.8	1.0	4AG		1.70	2.88	18.17	
	92060	392.7	394.2	1.5	1.5	4A4		2.50	6.42	29.14	
	92061	394.2	395.7	1.5	1.5	4A4		3.60	8.77	51.42	
	92062	395.7	397.3	1.6	1.5	4A4		2.13	5.25	39.42	
	92063	397.3	398.8	1.5	1.2	4A4		1.63	4.80	25.37	
FAGA065	92017	125.6	126.5	.9	.9	4G4		10.50	10.11		115.90
	92018	126.5	128.0	1.5	.6	4G#4		6.00	5.64		74.70
	92019	128.0	128.9	.9	.4	4G#4		4.80	2.46		58.60
	92020	128.9	130.5	1.6	1.0	4G#4		8.42	5.40		94.60
	92021	130.5	132.2	1.7	1.4	4G#4		6.53	3.78		84.70
	92022	164.3	165.2	.9	.2	4A14		3.75	1.56	37.40	
	92023	165.2	167.6	2.4	.2	4A14		4.20	1.54	40.40	
FAGA066	90155	68.3	70.0	1.7	.0	4A4		2.10	4.44	23.30	
	90156	88.6	89.5	.9	.0	4A34		5.63	5.52	61.40	
	90157	106.2	107.2	1.0	.0	4DEA4		4.65	5.82	54.40	
	90158	156.4	158.2	1.8	.0	4E#4		1.75	3.00	25.40	
	90159	158.2	159.6	1.4	.0	4E#4		5.70	7.20	72.70	
FAGA067	91573	224.1	285.0	.9	.0	4E64		4.13	5.88	60.00	
	91574	182.8	184.9	2.1	.0	4A14		2.33	3.90	34.00	
	91575	186.5	189.0	2.5	.0	4A14		2.18	4.26	33.00	
	91576	194.2	196.0	1.8	.0	4A14		2.15	4.62	35.00	
FAGA068	90041	128.5	129.8	1.3	1.3	4E4		7.71	12.62		105.90
	90042	188.7	190.2	1.5	1.5	4D0		3.30	4.80	40.40	
	90043	203.5	205.2	1.7	1.6	4A4		8.00	7.80	110.00	
	90044	205.2	206.8	1.6	1.6	4A4		8.15	15.38	121.00	
	90045	206.8	208.0	1.2	1.2	4A4		3.30	5.22	64.50	
	90046	215.3	217.4	2.1	2.1	4A4		7.63	9.81	102.80	
	90047	217.4	219.3	1.9	1.9	4A4		10.23	19.00	141.20	
	90048	219.3	219.9	.6	.6	4A4		10.06	12.46	121.00	
	90049	241.0	242.4	1.4	1.3	4EG4		4.73	6.00	75.80	
	90050	242.4	244.0	1.6	1.6	4EG4		5.10	8.30	70.60	
	90051	247.5	249.5	2.0	2.0	4E4		5.63	10.47	75.80	
FAGA069	90266	334.9	337.0	2.1	.0	4L2		.82	1.56		14.10
	90267	339.5	342.6	3.1	.0	4L2		.62	1.11		12.00
	90268	350.8	352.3	1.5	.0	4L1		.23	.25		2.10
	91022	137.8	138.6	.8	.8	4D4		6.31	8.39	91.90	
	91023	160.8	162.2	1.4	.0	4D0		2.43	4.62	35.30	
	91024	207.3	209.2	1.9	1.8	4A4		2.30	5.58	44.20	
	91025	220.2	221.4	1.2	.9	4AD4		8.58	24.07		111.10
	91026	222.9	223.8	.9	.9	4A4		5.74	14.43	105.90	
	91027	231.3	232.2	.9	.9	4D4		9.25	19.60	145.00	
	91028	312.4	314.2	1.8	1.8	4E4		5.95	9.13	83.60	
	91066	314.2	315.3	1.1	1.1	4E4		5.48	9.51	82.60	
FAGA070	90141	61.4	62.0	.6	.0	4A4		4.58	8.00	60.30	
	90142	79.2	81.7	2.5	.0	4LA		1.88	4.38	30.20	

DDH	SAMPLE	----DEPTHS----		INT	REC	ROCK UNIT	CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT
		FROM	TO								
FAGA070	90143	64.8	66.6	1.8	.0	4AE4		6.59	14.70	112.80	
FAGA071	91078	120.6	121.6	1.0	1.0	4E4		8.77	18.14		131.00
	91079	129.5	130.4	.9	.0	4C0		1.48	2.40		22.30
FAGA072	90371	154.3	156.4	2.1	.0	4AE		9.53	18.11	126.10	
	90372	156.4	156.7	.3	.0	4AE		5.64	12.45	79.50	
	90373	160.9	162.0	1.1	.0	4A34		2.15	4.20	30.20	
	90374	185.5	186.2	.7	.0	4A4		4.73	4.98	82.60	
FAGA073	90052	35.7	36.7	1.0	.5	4AG		.54	1.04		8.90
	90053	36.7	38.4	1.7	1.0	4AG		1.43	2.73		24.30
	90054	38.4	39.3	.9	.6	4A4		1.60	3.42		32.20
	90055	39.3	41.1	1.8	.7	4A4		1.83	4.32		35.30
	90056	41.1	42.7	1.6	.8	4AG		1.38	1.30		27.40
	90057	46.0	46.9	.9	.8	4E4		3.60	9.54		66.50
	90058	75.3	77.1	1.8	1.7	5C3		.35	.42		3.10
	90059	77.1	79.9	2.8	2.7	4E4		8.86	14.93		128.20
	90060	79.9	81.4	1.5	1.5	4D4		4.20	5.28		58.60
	90061	81.4	84.4	3.0	3.0	4D4		3.45	7.32		50.40
	90062	84.4	86.4	2.0	2.0	4D4		4.13	7.30		55.50
	90063	86.4	88.1	1.7	1.7	4D4		1.95	5.76		25.40
	90064	88.9	90.5	1.6	1.2	4A4		2.15	4.86		32.20
	90065	90.5	92.4	1.9	1.8	4A4		2.08	3.48		28.10
	90066	92.4	94.2	1.8	1.8	4A4		5.93	12.58		90.80
	90067	94.2	95.3	1.1	.7	4A4		2.78	5.16		44.20
	90068	95.3	97.4	2.1	.9	4A4		2.93	7.68		46.30
	90069	98.6	99.5	.9	.4	5C@4		1.00	4.26		18.20
	90070	100.1	100.6	.5	.5	5C@4		2.40	7.02		39.40
	90071	100.6	103.5	2.9	2.9	4D4		5.84	10.45		88.80
FAGA075	90462	26.2	27.7	1.5	1.5	4A4		2.28	5.58	40.40	
	90463	27.7	29.0	1.3	1.3	4A4		1.60	3.84	26.10	
	90464	29.0	30.5	1.5	1.5	4A4		2.00	4.02	31.20	
	90465	30.5	32.6	2.1	2.1	4A4		1.85	3.90	30.20	
	90466	32.6	35.1	2.5	2.5	4AL		1.23	3.30	15.10	
	90467	35.1	36.0	.9	.9	4L14		2.20	3.48	34.30	
	90468	36.0	37.5	1.5	1.5	4L14		2.35	4.32	31.20	
	90469	37.5	39.0	1.5	1.5	4L14		1.65	3.06	24.30	
	90470	39.0	40.8	1.8	1.8	4A4		1.23	4.59	18.20	
	90471	40.8	42.1	1.3	1.3	4A4		2.18	5.88	31.20	
	90472	42.1	43.6	1.5	1.5	4AG		1.48	3.48	24.30	
	90473	43.6	44.8	1.2	1.2	4A4		1.63	3.78	24.30	
	90474	44.8	45.9	1.1	1.1	4A4		2.20	5.76	39.40	
	90475	45.9	47.2	1.3	1.3	5D4@		.34	1.90	6.20	
	90476	47.2	48.8	1.6	1.6	4AD		3.30	5.22	50.40	
	90477	48.8	50.4	1.6	1.6	4C0		.28	.96	5.10	
	90478	50.4	51.5	1.1	1.1	4D0		2.93	5.88	45.30	
	90479	53.6	56.7	3.1	3.1	4AG		1.60	1.96	21.30	
	90480	56.7	58.8	2.1	2.1	4AG		1.48	3.36	22.30	
	90481	58.8	59.6	.8	.8	4A4		1.93	4.50	34.30	
	90482	59.6	61.3	1.7	1.7	4A4		3.90	9.08	64.50	
	90483	61.3	62.8	1.5	1.5	4A4		3.15	5.16	43.20	
	90484	62.8	64.9	2.1	2.1	4A4		4.35	6.36	57.60	
	90485	64.9	67.7	2.8	2.8	4A4		1.95	3.30	30.20	

DDH	SAMPLE	----DEPTHS----		INT	REC	ROCK UNIT	CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT
		FROM	TO								
FAGA075	90486	68.4	69.8	1.4	1.4	4L41		2.85	4.50	37.40	
	90487	69.8	71.6	1.8	1.8	4AL		2.13	3.96	35.30	
	90488	71.6	72.8	1.2	1.2	4L41		1.40	3.54	20.20	
	90489	72.8	73.9	1.1	1.1	4L41		2.43	5.40	35.30	
	90490	75.1	75.9	.8	.8	4L41		1.45	4.74	20.20	
	90491	75.9	77.4	1.5	1.5	4L41		3.60	10.82	50.40	
	90492	77.4	78.9	1.5	1.2	4L41		3.60	7.08	60.20	
	90493	78.9	80.5	1.6	1.5	4L41		3.45	5.64	51.40	
	90494	80.5	82.1	1.6	1.6	4A41		4.05	7.08	56.60	
	90495	82.1	84.1	2.0	2.0	5D40		.70	2.58	9.90	
	90496	84.1	85.8	1.7	1.7	4A4		4.43	7.68	60.30	
	90497	85.8	87.8	2.0	2.0	4A4		2.33	4.44	34.30	
	90498	87.8	89.1	1.3	1.3	4L14		3.53	6.48	47.30	
	90499	89.1	90.8	1.7	1.7	4L14		4.99	8.76	70.60	
	90500	90.8	91.9	1.1	1.1	4L14		3.68	7.80	48.30	
	90501	92.3	93.9	1.6	1.6	4A4		1.63	3.60	24.30	
	90502	93.9	96.3	2.4	2.4	4A0		1.10	3.12	15.10	
	90503	96.3	97.8	1.5	1.5	4A4		2.25	7.08	34.30	
	90504	97.8	99.1	1.3	1.3	4D0		3.23	6.72	40.40	
	90505	99.1	100.3	1.2	1.2	4L14		3.98	6.60	52.40	
	90506	100.3	103.3	3.0	3.0	4A4		6.09	14.43	80.60	
	90507	103.3	104.7	1.4	1.4	4A43		3.23	8.97	53.50	
	90508	104.7	106.2	1.5	1.5	4A43		2.38	5.34	35.30	
	90509	106.2	107.7	1.5	1.5	4A43		4.95	6.36	59.30	
	90510	107.7	108.7	1.0	1.0	4A43		2.85	5.64	45.30	
	90511	109.1	110.9	1.8	1.8	4A4		3.08	5.88	40.40	
	90512	245.0	246.5	1.5	1.5	4E4		12.75	9.23	171.40	
	90513	249.0	250.6	1.6	1.6	4K4		6.68	5.16	78.50	
90514	250.6	252.2	1.6	1.6	4AK		6.08	4.20	67.50		
90515	253.0	253.6	.6	.6	4AD		4.13	10.89	59.70		
90516	253.6	254.7	1.1	1.1	4G4		3.90	7.44	57.60		
90517	259.4	261.4	2.0	2.0	4G4		5.40	10.50	81.60		
90518	261.4	262.5	1.1	1.1	4AG		4.50	8.23	67.50		
90519	262.8	264.3	1.5	1.5	4G4		4.80	7.62	70.60		
90520	264.3	264.9	.6	.6	4G4		5.10	8.56	74.70		
FAGA076	91029	139.5	140.5	1.0	.0	4G48		6.70	10.65		62.40
	91030	140.5	142.1	1.6	.0	4E4		4.65	7.20		66.50
	91031	142.1	143.6	1.5	.0	4A4		3.75	5.28	52.40	
	91032	284.5	285.4	.9	.9	4A4		6.94	7.68	91.90	
	91033	285.8	287.4	1.6	.0	4D34		5.18	4.92	63.40	
	91034	337.8	338.3	.5	.0	4DE4		6.44	11.65		68.60
	91035	338.3	339.2	.9	.0	4A10		.02	.06		1.00
	91036	341.8	344.0	2.2	.0	4DE		2.35	3.48		35.30
	91037	364.8	366.5	1.7	.0	4E46		4.35	4.44		52.40
	91038	367.8	369.4	1.6	.0	4GC		3.15	3.06		40.40
	91039	369.4	370.6	1.2	.0	4GC		1.00	.31		12.00
	91040	370.6	372.2	1.6	.0	4EG		4.73	3.60		48.30
	91041	372.2	373.4	1.2	.0	4C3		1.60	.22		9.90
	91042	373.4	374.4	1.0	.0	4G08		5.37	4.20		48.30
	91043	374.4	375.7	1.3	.0	4C3		.59	.27		11.00
91044	375.7	377.3	1.6	.0	4G08		5.03	3.66		50.40	
91045	377.3	378.7	1.4	.0	4G08		4.05	3.42		39.40	
FAGA078	91577	51.7	53.2	1.5	-.5	4D4		5.40	9.22	90.80	

DDH	SAMPLE	---DEPTHS---		INT.	REC	ROCK UNIT	CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT
		FROM	TO								
FAGA078	91578	54.6	55.3	.7	-.5	4D4		6.38	13.30	90.80	
	91579	56.8	58.0	1.2	-.5	4D4		3.90	8.04	59.70	
	91580	74.6	76.1	1.5	-.5	4D47		5.03	4.80	65.50	
	91581	78.6	80.8	2.2	-.5	4D45		8.72	14.83	126.10	
	91582	80.8	82.6	1.8	-.5	4A4		2.45	4.14	37.40	
	91583	82.6	84.0	1.4	-.5	4D4		3.90	6.84	54.50	
	91584	84.0	85.3	1.3	-.5	4A4		1.68	4.20	28.10	
	91585	85.3	86.0	.7	-.5	4AC		1.83	3.00	27.10	
	91586	262.7	263.9	1.2	-.5	4G4		5.10	5.40	64.50	
	91587	264.1	264.9	.8	-.5	4L42		1.83	3.18	25.40	
	91588	265.2	266.7	1.5	-.5	4L42		1.23	3.00	20.20	
	91589	266.7	267.6	.9	-.5	4E4		3.75	6.36	75.80	
	91590	284.1	286.1	2.0	-.5	4A43		5.25	7.20	89.80	
	91591	286.1	287.4	1.3	-.5	4A30		1.50	3.00	20.20	
	91592	287.4	289.0	1.6	-.5	4A34		1.88	3.24	24.30	
	91593	289.0	290.2	1.2	-.5	4A34		1.90	3.72	26.10	
	91594	290.2	291.4	1.2	-.5	4A30		1.15	1.18	20.20	
	91595	291.4	293.5	2.1	-.5	4A34		1.80	4.38	31.20	
	91596	293.5	294.1	.6	-.5	4LG		.59	.94	8.20	
	FAGA079	91046	89.3	90.8	1.5	1.5	4A4		3.30	5.46	
91047		90.8	92.5	1.7	1.7	4A4		2.93	5.40		37.40
91048		92.5	96.0	3.5	1.4	4A4		4.13	2.82		44.20
91049		96.0	97.4	1.4	1.3	4AG		1.58	1.94		25.40
91050		97.4	99.4	2.0	2.0	4AC		1.35	2.46		23.30
91051		99.4	100.9	1.5	1.5	4A4		2.50	4.26		35.30
91052		100.9	102.4	1.5	.0	4AO		1.48	3.00		21.30
91053		102.4	104.5	2.1	1.8	4A4		1.90	4.14		29.10
91054		106.8	109.7	2.9	2.6	4AO		.93	1.84		15.10
91055		114.1	115.7	1.6	1.5	4AC		1.19	3.60		20.20
91056		115.7	116.9	1.2	1.2	4A4		4.50	5.28		60.30
91057		118.1	119.5	1.4	1.3	4DG		2.78	6.48		49.40
91058		119.5	121.7	2.2	2.2	4DE		6.17	10.92		100.80
91059		286.5	287.6	1.1	1.0	4AC		.85	1.74		12.00
91060		287.6	289.4	1.8	1.8	4AD		2.23	4.26		39.40
91061		289.8	291.8	2.0	1.9	4A4		2.28	3.60		36.30
91062	291.8	292.4	.6	.6	4AC		2.33	2.46		28.10	
91063	344.6	346.3	1.7	1.6	4E48		5.84	5.40	61.40		
FAGA082	90375	333.3	334.8	1.5	.0	4E81		2.20	3.78		23.30
	90376	334.8	336.3	1.5	.0	4C78		1.45	2.73		18.20
	90377	114.3	115.8	1.5	.0	4A4		1.63	3.60		33.30
	91597	97.5	98.3	.8	.0	4D7		2.78	5.04	20.20	
	91598	102.2	103.9	1.7	.0	4C0		1.80	3.06	28.50	
	91599	103.9	105.2	1.3	.0	4D0		1.98	3.42	28.50	
	91600	118.7	120.7	2.0	.0	4E4		6.15	10.37	91.90	
	91601	121.8	123.4	1.6	.0	4D0		2.08	3.30	44.20	
	91602	123.4	124.9	1.5	.0	4D0		2.05	3.12	44.20	
	91603	137.1	138.9	1.8	.0	4AE		3.30	6.45	41.50	
	91604	273.4	274.1	.7	.0	4G4		4.72	9.40	90.80	
	91605	292.2	293.7	1.5	.0	4A4		3.53	4.44	54.50	
	91606	293.7	295.2	1.5	.0	4A4		2.23	4.44	33.30	
	91607	320.7	322.2	1.5	.0	4E46		4.92	6.35	72.70	
91608	327.2	328.7	1.5	.0	4E48		4.28	3.18	45.30		
91609	328.7	330.3	1.6	.0	4D0		3.98	1.34	40.40		

DDH	SAMPLE	----DEPTHS----		INT	REC	ROCK UNIT	CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT
		FROM	TO								
FAGA082	91610	330.3	331.8	1.5	.0	4E81		1.38	1.86	16.10	
	91611	331.8	333.3	1.5	.0	4E81		1.34	1.56	19.20	
FAGA083	90176	240.4	241.1	.7	.7	4A1		.10	.46		5.10
	92024	138.2	140.8	2.6	2.6	4E4		5.20	3.66		72.70
	92025	141.3	144.3	3.0	3.0	4E4		3.53	3.12		44.20
FAGA084	90367	215.6	216.7	1.1	.0	4L14		3.08	4.86	45.30	
	90368	216.7	219.2	2.5	.0	4G4		5.63	8.88	91.90	
	90369	253.4	254.6	1.2	.0	5B49		1.30	1.84	20.20	
	90370	254.6	255.8	1.2	.0	4E47		4.93	5.10	54.50	
FAGA085	90414	196.9	198.9	2.0	.0	4C0		.25	.62	6.20	
	90415	198.9	201.9	3.0	.0	4C0		.40	1.08	8.90	
	90416	201.9	205.0	3.1	.0	4C5		.83	.94	13.00	
	90417	205.0	208.0	3.0	.0	4C5		.43	.68	5.10	
	90418	208.0	211.1	3.1	.0	4C5		.44	1.14	6.20	
	90419	211.1	214.1	3.0	.0	4C0		.44	1.10	5.10	
	90420	214.1	217.2	3.1	.0	4C0		.80	1.16	12.00	
	90421	217.2	218.8	1.6	.0	4D0		2.48	5.82	34.30	
	90422	219.9	221.9	2.0	.0	3G0		.19	.33	1.00	
	90423	221.9	224.5	2.6	.0	3G0		.22	.48	2.10	
	90424	258.0	261.1	3.1	.0	4C0		.60	1.10	9.90	
	90425	261.1	262.7	1.6	.0	4C0		.38	.61	7.20	
	90426	262.7	264.6	1.9	.0	4A4		3.83	3.96	47.30	
	90427	264.6	266.2	1.6	.0	4A4		2.38	3.72	30.20	
	90428	266.2	268.6	2.4	.0	4A4		4.73	5.40	65.50	
	90429	268.6	270.6	2.0	.0	4A0		.98	1.68	17.10	
	90430	270.6	273.6	3.0	.0	4C0		.34	.28	6.20	
	90431	273.6	277.7	4.1	.0	4A0		1.20	1.42	23.30	
	90432	281.6	284.7	3.1	.0	4A30		1.38	1.40	21.30	
	90433	292.9	296.0	3.1	.0	4A4		4.13	3.96	45.30	
	90434	299.3	302.8	3.5	.0	4A4		2.78	2.82	36.30	
	90435	338.1	340.9	2.8	.0	4D4		4.43	6.75	65.50	
	90436	340.9	343.8	2.9	.0	4D43		5.25	6.96	65.50	
	90437	343.8	346.3	2.5	.0	4D43		5.23	11.53	80.60	
90438	346.3	347.5	1.2	.0	4D43		4.85	7.48	64.50		
90439	348.1	351.1	3.0	.0	4D43		5.98	9.03	80.60		
90440	351.1	352.3	1.2	.0	4E4		4.54	7.68	55.50		
90441	357.0	357.8	.8	.0	4D45		6.35	9.97	90.80		
90442	360.6	361.6	1.0	.0	4D0		3.87	4.62	61.40		
90443	366.5	368.5	2.0	.0	4L57		.43	.26	7.20		
90444	368.5	369.1	.6	.0	4L57		.65	1.13	14.10		
90445	390.8	391.5	.7	.0	4A0		.63	1.06	8.90		
90446	391.5	392.4	.9	.0	4E47		5.12	3.96	50.70		
90447	393.5	395.2	1.7	.0	4E4		4.65	3.66	51.40		
90448	400.2	400.7	.5	.0	4E80		2.78	2.76	35.30		
90449	239.6	242.8	3.2	.0	4D5		3.00	3.96	36.30		
FAGA086	92064	376.5	379.7	3.2	3.2	3G6		.43	.33	4.11	
	92065	379.7	380.8	1.1	1.0	4E1		2.25	3.48	30.17	
	92066	380.8	383.0	2.2	2.2	4A4		2.08	4.14	31.19	
	92067	383.0	384.5	1.5	1.5	4A0		1.58	2.70	23.31	
	92068	384.5	385.9	1.4	1.4	4A0		1.78	3.18	25.37	
	92069	385.9	387.0	1.1	1.0	4A0		1.65	2.94	24.34	

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK UNIT	CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT
		FROM	TO								
FAGA086	92070	387.0	388.9	1.9	1.8	4D0		1.60	4.62	21.25	
	92071	388.9	391.8	2.9	2.9	4E1					
	92072	392.4	393.3	.9	.9	4E1					
	92073	393.9	398.0	4.1	4.1	4EC					
	92074	508.8	509.7	.9	.0	4Q\$43		3.75	4.68	34.28	
FAGA087	90390	163.6	165.0	1.4	1.4	4D4		5.37	9.26	81.60	
	90391	165.0	165.7	.7	.6	4D4		4.35	5.60	70.60	
	90392	165.7	166.4	.7	.7	4A4		2.93	3.12	45.30	
	90393	178.7	179.6	.9	.9	4A4		3.45	5.64	55.50	
	90394	199.2	202.2	3.0	2.9	4D5		3.00	4.26	41.50	
	90395	202.2	203.0	.8	.8	4D5		2.00	2.22	26.40	
	90396	203.0	206.0	3.0	3.0	4D5		3.08	3.90	43.50	
	90397	219.9	222.8	2.9	2.9	4D0		3.90	3.48	75.80	
	90398	222.8	225.7	2.9	2.9	4D0		2.38	6.66	42.50	
	90399	229.8	232.0	2.2	2.1	4D4		4.20	8.36	75.80	
	90400	232.0	233.5	1.5	1.5	4D0		2.08	7.26	45.30	
	90401	237.3	239.3	2.0	1.9	4E4		7.33	14.54	112.40	
	90402	317.6	319.4	1.8	1.8	4GE4		4.13	6.15	82.60	
	90403	319.4	320.9	1.5	1.4	4GE4		4.80	7.70	111.10	
	90404	320.9	322.6	1.7	1.7	4GE		3.15	5.16	52.40	
	90405	322.6	323.0	.4	.3	4E0		2.78	.50	50.40	
90406	323.7	324.1	.4	.4	4E0		.11	.04	4.20		
90407	324.1	326.9	2.8	2.8	4G4		4.28	5.28	71.70		
90408	326.9	327.5	.6	.6	4E0		.73	.28	21.30		
90409	328.8	330.6	1.8	1.7	4A4		5.71	6.48	85.70		
90410	330.6	331.9	1.3	1.3	4GE4		4.58	7.68	72.70		
90411	331.9	335.0	3.1	3.0	4GE4		4.73	8.48	85.70		
90412	335.0	337.0	2.0	1.9	4A34		4.65	10.07	95.60		
90413	337.0	337.6	.6	.6	4AL		.75	1.42	14.10		
FAGA088	90146	116.4	118.1	1.7	1.5	4EA4		5.70	9.55		79.50
	90147	118.1	120.1	2.0	1.5	4EA4		2.00	3.90		22.30
	90148	204.1	204.8	.7	.3	4A4		4.28	6.55		57.60
	90149	204.8	205.7	.9	.8	4DE4		5.68	8.77		80.60
	90150	205.7	208.0	2.3	2.3	4DE4		7.87	10.83		103.90
	90151	208.0	208.8	.8	.6	4DE4		5.03	5.40		57.60
	90152	209.4	210.0	.6	.5	4DE4		5.64	6.24		67.50
	90153	327.4	329.2	1.8	1.8	4L2		.13	.37		4.10
FAGA089	90450	343.0	344.4	1.4	.0	4AC		.05	.36	1.00	
	90451	344.4	347.7	3.3	.0	4AC		.21	.38	8.20	
	90452	347.7	349.8	2.1	.0	4C0		.03	.03	1.00	
	90453	352.7	356.7	4.0	.0	4A0		.08	.14	3.10	
	90455	356.7	357.6	.9	.0	4C0		.09	.16	1.00	
	90456	377.2	378.0	.8	.8	4EC		.70	.52	19.20	
	90459	163.7	165.5	1.8	.0	4CE		.93	1.74	15.10	
	90460	165.5	168.0	2.5	.0	4EC		1.13	1.14	22.30	
90461	259.0	260.7	1.7	.0	4D4#\$		5.03	9.50	72.70		
FAGA093	90457	289.3	289.7	.4	.0	4E4		4.88	4.56	75.80	
	90458	289.7	290.8	1.1	.0	4L12		4.88	4.56	75.80	
FAGA096	90138	148.4	149.1	.7	.0	4D4		9.63	22.37	177.60	
	90139	149.1	150.3	1.2	.0	4D4		7.53	17.61	125.10	

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK UNIT	CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT
		FROM	TO								
FAGA096	90140	150.3	151.5	1.2	.0	4D4		7.20	17.92	142.30	
FAGA097	92075	19.1	20.4	1.3	1.3	4L67		1.40	1.54	30.17	
	92076	20.4	22.4	2.0	2.0	4L67		.50	.38	30.17	
	92077	22.4	23.5	1.1	1.0	4L6		.10	.18	8.23	
FAGA098	92078	24.2	26.8	2.6	2.6	4DEG		2.70	2.64	35.31	
FAGA099	90357	62.4	64.0	1.6	1.6	4A4		1.33	4.38		21.30
FAGA111	90599	271.9	273.9	2.0	2.0	4CA0		.80	1.46	19.20	
	90600	273.9	275.4	1.5	1.5	4CA0		.85	1.14	8.90	
	90601	275.4	276.2	.8	.8	4CA0		1.03	1.72	12.00	
	90602	277.8	279.8	2.0	2.0	4CA0		1.00	1.10	15.10	
	90603	279.8	281.0	1.2	1.2	4AC0		.78	.96	14.10	
	90604	281.0	282.1	1.1	1.1	4AC0		.88	1.12	13.00	
FAGA123	91213	113.2	115.0	1.8	1.8	4D0		2.38	3.48	37.40	
	91214	115.0	116.0	1.0	1.0	4C0		1.83	2.00	24.30	
	91215	116.0	118.0	2.0	2.0	4D0		1.93	3.54	26.40	
	91216	118.0	120.0	2.0	2.0	4D0		1.90	3.48	29.10	
	91217	120.0	122.0	2.0	2.0	4C0		1.75	3.18	26.40	
	91218	122.0	124.0	2.0	2.0	4C0		1.99	3.00	28.50	
	91219	127.6	128.9	1.3	1.3	4C0		1.84	2.76	29.10	
	91220	128.9	130.0	1.1	1.1	4C0		1.48	2.46	24.30	
	91221	132.6	134.4	1.8	.5	4C0		1.23	1.66	28.50	
	91222	134.4	135.9	1.5	.9	4A4		2.50	4.02	36.30	
	91223	135.9	136.8	.9	.7	4A4		2.48	5.40	35.30	
	91224	136.8	137.8	1.0	.5	4C5		1.78	2.76	28.50	
	91225	137.8	139.3	1.5	1.5	4AC		1.93	2.46	30.20	
	91226	139.3	141.4	2.1	1.5	4A4		2.45	3.18	37.40	
	91227	141.4	142.3	.9	.8	4A4		2.59	3.90	41.50	
	91228	142.3	144.5	2.2	.6	4A4		2.70	4.02	43.50	
	91229	144.5	145.4	.9	.9	4D0		3.53	5.93	65.50	
	91230	145.4	146.6	1.2	.4	4A4		2.78	4.02	46.30	
	91231	150.6	151.5	.9	.9	4Q\$		1.23	1.18	21.30	
	91232	156.5	158.5	2.0	1.8	4A4		2.50	4.38	40.40	
	91233	158.5	160.0	1.5	1.4	4A4		2.78	4.20	44.20	
	91234	160.0	160.7	.7	.7	4AG		1.73	2.64	29.10	
	91235	188.5	189.4	.9	.8	4D0		1.53	3.48	19.20	
	91236	189.4	191.1	1.7	1.7	4D0		2.18	5.40	31.20	
	91237	191.6	193.5	1.9	.3	4D0		2.93	5.64	33.30	
	91238	193.5	194.5	1.0	.6	4D4		23.00	7.20	50.40	
	91239	194.5	195.7	1.2	1.1	4D4		3.75	8.00	63.40	
	91240	195.7	196.3	.6	.6	4D0		4.58	4.02	59.30	
	91241	196.3	197.6	1.3	1.3	4D0		2.85	2.40	33.30	
	91242	197.6	200.1	2.5	1.2	4AG		1.93	2.14	28.50	
	91243	200.1	201.5	1.4	1.4	4A4		2.48	5.76	46.30	
	91244	201.5	203.3	1.8	1.8	4A4		1.88	4.68	34.30	
	91245	203.3	204.2	.9	.5	4A4		1.70	4.08	26.40	
	91246	204.2	205.5	1.3	1.3	4A4		2.18	1.47	25.40	
	91247	209.4	211.2	1.8	1.8	4D0		3.60	3.60	38.40	
	91248	229.6	230.7	1.1	1.1	4D0		2.85	6.29	48.30	
	91249	230.8	231.9	1.1	1.1	4D0		2.63	4.50	36.30	
	91250	231.9	233.5	1.6	1.6	5D4\$		1.23	1.40	18.20	

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK UNIT	CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT
		FROM	TO								
FAGA123	91251	233.5	234.2	.7	.7	4D4		5.71	7.18	88.80	
	91252	234.6	236.1	1.5	1.5	4A0		1.18	1.70	19.20	
	91253	236.1	237.6	1.5	1.5	3G0		.58	.76	7.20	
	91254	239.1	239.9	.8	.8	4C0		2.38	2.14	33.30	
	91255	244.0	246.0	2.0	2.0	4AD		4.65	6.90	68.60	
	91256	246.0	248.0	2.0	2.0	4A4		4.73	8.11	77.80	
	91257	248.0	250.0	2.0	2.0	4A4		4.20	8.07	64.50	
	91258	250.0	251.8	1.8	1.8	5B26		.75	1.54	12.00	
	91259	251.8	253.0	1.2	1.2	4A44		7.73	16.75	143.30	
	91260	253.0	254.0	1.0	1.0	4A4		2.70	4.02	46.30	
	91261	273.1	274.6	1.5	1.5	4E4		5.21	11.86	84.70	
	91262	274.6	275.7	1.1	1.1	4E4		6.93	14.44	123.10	
	91263	278.0	279.3	1.3	1.3	4A4		2.43	5.64	38.40	
	91264	279.3	281.0	1.7	1.7	4D4		5.11	6.05	76.80	
	91265	281.0	282.5	1.5	1.5	4AD		3.75	5.86	58.60	
	91266	282.5	284.0	1.5	1.5	4A4		4.35	5.64	73.70	
	91267	284.0	285.6	1.6	1.5	4A4		4.95	7.58	85.70	
	91268	285.6	286.7	1.1	1.1	4A4		3.68	7.69	68.60	
	91269	299.1	300.4	1.3	1.3	4A4		2.63	3.42	44.20	
	91270	300.4	302.0	1.6	1.3	4C5		1.15	2.10	18.20	
	91271	302.0	304.0	2.0	1.9	4A0		1.88	2.76	30.20	
	91272	304.0	306.0	2.0	2.0	4A4		3.15	4.92	50.40	
	91273	306.0	307.2	1.2	1.2	4A4		3.98	6.23	60.30	
	91274	316.3	317.8	1.5	1.5	3G46		.40	1.36	5.10	
	91275	317.8	319.4	1.6	1.6	3G46		.38	.95	4.10	
	91276	320.6	322.6	2.0	2.0	4L74		.50	.92	8.90	
	91277	322.6	324.5	1.9	1.9	4L74		.23	.52	5.10	
	91278	374.0	375.2	1.2	1.2	3C4\$		1.68	1.92	25.40	
	91279	375.2	376.4	1.2	1.2	4G4		7.65	11.53	126.10	
	91280	376.4	377.4	1.0	1.0	4G4		4.95	5.76	68.60	
91281	378.9	380.2	1.3	1.2	4E\$4		3.83	2.10	50.40		
91282	383.4	384.1	.7	.7	4E\$4		7.41	3.18	106.90		
91283	384.8	385.6	.8	.8	4E\$4		2.48	3.48	42.50		
91284	385.6	386.8	1.2	1.2	3C2		.70	1.28	15.10		
91285	390.4	391.7	1.3	1.3	4E0		1.95	3.06	33.30		
91286	391.7	392.9	1.2	1.2	4E4		3.15	3.12	45.30		
91287	392.9	394.6	1.7	1.7	4A43		4.92	8.35	76.80		
91288	399.0	400.2	1.2	1.2	4A30		.65	1.00	29.10		
91289	400.2	402.0	1.8	1.8	4C3		.68	1.44	20.20		
91290	402.8	404.0	1.2	1.2	4EG		3.98	4.86	52.40		
91291	404.0	405.5	1.5	1.5	4E8		1.88	1.92	30.20		
91292	405.5	406.6	1.1	1.1	4G4		6.98	8.87	112.10		
91293	406.6	408.1	1.5	1.5	4G4		6.38	9.36	103.90		
91294	421.8	422.9	1.1	1.1	3G16		.45	.46	11.00		
91295	422.9	423.6	.7	.7	4E81		.65	.46	18.20		
91296	423.6	424.7	1.1	1.1	4A0		.55	.64	11.00		
91297	438.8	440.4	1.6	1.6	4HA		1.55	.64	11.00		
FAGA125	91172	113.8	115.2	1.4	1.3	4AD		3.00	6.85	53.50	
	91173	115.2	116.5	1.3	.9	4A5D		.83	1.94	15.10	
	91174	116.5	119.2	2.7	2.1	4A4		2.08	4.14	29.10	
	91175	119.2	122.2	3.0	2.9	4A4		1.98	4.74	31.20	
	91176	122.2	124.4	2.2	2.2	4D5		2.78	4.98	35.30	
	91177	124.4	126.6	2.2	2.2	4D5		2.08	3.42	31.20	
	91178	133.9	135.1	1.2	1.2	4A4		3.00	5.10	44.20	

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK UNIT	CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT
		FROM	TO								
FAGA125	91179	172.2	173.6	1.4	1.3	3G91		1.98	3.30	29.10	
	91180	173.6	175.0	1.4	1.3	4A4		2.38	5.10	37.40	
	91181	175.0	177.7	2.7	2.5	4A4		1.88	4.05	29.10	
	91182	227.0	227.7	.7	.7	4A4		3.53	4.30	54.50	
	91183	227.7	229.0	1.3	1.3	4AE		6.41	11.84	109.00	
	91184	229.5	231.0	1.5	1.5	4AC		.75	1.18	9.90	
	91185	317.6	318.6	1.0	1.0	4E14		5.42	6.50	90.80	
	91186	321.9	322.8	.9	.5	4D5		2.75	4.50	43.50	
	91187	322.8	324.8	2.0	1.9	4D5		3.44	5.55	49.40	
	91188	324.8	325.8	1.0	1.0	4C5		1.65	1.66	21.30	
	91189	326.6	328.6	2.0	2.0	4A3\$4		2.85	3.98	38.40	
	91190	328.6	331.1	2.5	2.5	4A3\$		1.63	2.10	28.50	
	91191	336.5	337.6	1.1	1.1	3G6		2.50	2.70	25.40	
	91192	340.6	342.6	2.0	1.9	4AD		1.38	2.20	16.10	
	91193	344.0	345.6	1.6	1.6	4D45		3.23	4.05	39.40	
	91194	355.1	355.7	.6	.6	4A3		.83	1.08	16.10	
	91195	355.7	356.7	1.0	1.0	4G4		5.18	8.75	85.70	
	91196	356.7	357.4	.7	.7	4G4		4.43	7.87	73.70	
	91197	357.6	358.6	1.0	1.0	4G0		3.98	5.00	56.60	
	91198	358.6	359.6	1.0	1.0	4G0		3.56	5.50	60.30	
	91199	359.6	360.9	1.3	1.3	4GA		3.94	6.57	61.40	
	91200	361.3	362.3	1.0	.6	4E4		2.38	4.40	40.40	
	91201	362.3	363.3	1.0	1.0	4E4		3.60	4.48	55.50	
	91202	363.3	364.3	1.0	1.0	4E4		3.30	6.28	50.10	
	91203	364.3	365.3	1.0	1.0	4E4		4.28	7.68	73.70	
	91204	365.3	366.0	.7	.7	4EG		5.18	7.56	94.60	
	91205	381.3	383.3	2.0	2.0	4AC		.48	.52	13.00	
	91206	383.3	385.3	2.0	2.0	4AC		.20	.18	12.00	
	91207	385.3	386.9	1.6	1.6	4AC		.65	.77	28.50	
	91208	386.9	388.2	1.3	1.3	4A43		6.96	9.44	98.70	
	91209	388.2	390.2	2.0	2.0	4AC		1.15	1.70	21.30	
	91210	390.2	392.6	2.4	2.4	4A7		.38	.62	14.10	
	91211	392.6	394.7	2.1	2.1	4ADH		3.83	2.88	46.30	
	91212	403.4	405.9	2.5	2.5	4E4		2.85	3.12	42.50	
FAGA127	91127	93.5	96.5	3.0	2.8	4CA		1.70	2.88	26.40	
	91128	96.5	99.5	3.0	2.8	4A4		1.78	4.50	40.40	
	91129	99.5	102.5	3.0	2.7	4D5		2.08	5.34	43.50	
	91130	102.5	105.5	3.0	.6	4C5		1.68	2.88	25.40	
	91131	105.5	108.5	3.0	3.0	4C5		1.20	3.30	26.40	
	91132	108.5	111.5	3.0	3.0	4D5		1.38	3.66	25.40	
	91133	111.5	114.5	3.0	3.0	4D5		1.68	4.20	38.40	
	91134	114.5	117.5	3.0	3.0	4D5		1.78	4.02	35.30	
	91135	117.5	120.5	3.0	2.9	4D5		1.58	3.96	29.10	
	91136	120.5	123.7	3.2	3.0	4D5		2.15	4.86	38.40	
	91137	162.5	165.8	3.3	3.3	4A0		1.28	3.54	23.30	
	91138	235.9	237.2	1.3	1.3	4AE		5.61	9.78	85.70	
	91139	237.2	240.7	3.5	3.4	4LA		.88	1.06	14.10	
	91140	240.7	242.6	1.9	1.9	4A4		2.63	3.54	47.30	
	91141	242.6	244.4	1.8	1.8	4D0		3.08	6.88	59.30	
	91142	245.4	246.0	.6	.6	4D0		2.30	6.84	48.30	
	91143	327.5	329.5	2.0	2.0	4A4		4.73	6.29	76.80	
	91144	329.5	332.4	2.9	2.5	4A4		3.68	4.56	56.60	
	91145	334.2	334.6	.4	.4	4E0		1.10	2.16	20.20	
	91146	334.6	336.6	2.0	1.8	4E4		7.13	10.56	126.10	

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK UNIT	CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT
		FROM	TO								
FAGA127	91147	336.6	337.7	1.1	1.1	4EG		8.78	18.74	146.00	
	91148	337.7	339.7	2.0	2.0	4EG		7.65	14.28	98.70	
	91149	339.7	341.5	1.8	1.8	4EG		7.20	15.57	96.70	
	91150	341.5	343.2	1.7	1.7	4AE		6.78	15.11	98.70	
	91151	343.2	345.2	2.0	2.0	4AG		4.73	9.36	74.70	
	91152	345.2	347.2	2.0	2.0	4AG		5.85	11.12	87.80	
	91153	347.2	348.4	1.2	1.2	4G4		5.40	8.39	102.80	
	91154	401.7	402.5	.8	.8	3G916		4.80	5.76	57.60	
	91155	402.5	403.4	.9	.9	4G4		5.33	5.16	70.60	
	91156	403.4	403.7	.3	.2	3C4\$		.25	.40	8.20	
	91157	403.7	404.7	1.0	1.0	4G0		4.43	4.14	75.80	
	91158	404.7	406.0	1.3	1.3	4G4		6.38	9.34	106.90	
	91159	406.0	408.2	2.2	2.2	4E86		1.78	.88	20.20	
	91160	408.2	408.9	.7	.7	4E86		.55	.53	12.00	
	91161	408.9	409.6	.7	.7	4E86		7.50	5.67	65.50	
	91162	409.6	410.6	1.0	1.0	4E48		5.97	6.59	60.30	
	91163	410.6	411.6	1.0	1.0	4C3		.35	.30	12.00	
	91164	411.6	412.6	1.0	1.0	4C3		.15	.14	8.90	
	91165	412.6	413.6	1.0	1.0	4C3		1.23	.72	23.30	
	91166	413.6	414.6	1.0	1.0	4C3		.43	.50	14.10	
91167	414.6	415.6	1.0	1.0	4C3		.48	1.25	16.10		
91168	415.6	416.6	1.0	1.0	4C3		1.18	.90	20.20		
91169	416.6	417.6	1.0	1.0	4C38		.75	.74	17.10		
91170	417.6	419.6	2.0	2.0	4C38		.53	.46	13.00		
91171	419.6	421.1	1.5	1.5	4CEG		1.35	1.54	28.50		
92085	89.4	90.5	1.1	1.0	4C0		1.88	2.94	23.31		
FAGA128	91100	237.8	239.8	2.0	1.9	4C#\$		.93	.65	14.10	
	91101	239.8	241.0	1.2	1.2	4E8		2.45	1.63	35.30	
	91102	241.0	242.1	1.1	1.1	4G4		6.08	8.00	106.90	
	91104	246.2	247.5	1.3	1.1	4D\$		2.23	3.28	28.50	
	91105	317.6	318.2	.6	.3	4EG		7.25	8.32	148.10	
	91106	318.2	318.8	.6	.5	4J24		15.59	23.00	302.40	
	91107	347.8	348.8	1.0	.9	4ED		4.13	4.86	53.50	
	91108	352.2	353.6	1.4	1.2	4DA		1.58	1.50	22.30	
	91109	353.6	355.1	1.5	1.4	4A10		1.13	1.08	21.30	
	91110	355.1	356.6	1.5	1.3	4AD		1.31	1.50	19.20	
	91111	356.6	360.0	3.4	2.3	4DAC		3.13	5.40	42.50	
	91112	360.0	361.5	1.5	1.3	4C\$		1.65	2.38	26.40	
	91113	361.5	362.1	.6	.6	4E4#		8.10	9.68	99.70	
	91114	363.0	365.0	2.0	2.0	4G4		5.18	6.16	65.50	
	91115	367.1	368.3	1.2	1.2	4E4a		6.74	8.65	100.80	
	91116	368.3	370.0	1.7	1.6	4D\$		2.06	2.90	26.40	
	91117	419.7	422.3	2.6	2.6	4C0		1.13	2.68	18.20	
	91118	425.8	426.8	1.0	1.0	4L\$24		1.33	2.70	20.20	
	91119	426.8	428.3	1.5	1.5	4EG		3.08	3.54	51.40	
	91120	428.3	429.8	1.5	1.5	4EG		2.70	4.65	43.50	
91121	431.7	433.4	1.7	1.7	4E8		2.56	2.22	27.40		
91122	435.8	436.6	.8	.8	4E4		3.00	3.42	34.30		
91123	436.6	437.6	1.0	1.0	4E4		4.13	2.46	40.40		
91124	437.6	438.6	1.0	1.0	4E4		3.98	3.20	35.30		
91125	438.6	439.6	1.0	1.0	4E4		5.89	6.32	50.40		
91126	444.7	445.9	1.2	1.2	4AC		3.30	2.52	36.30		
FAGA131	90605	115.2	117.0	1.8	.3	4A4		2.95	4.60	33.30	

DDH	SAMPLE	----DEPTHS----		INT	REC	ROCK UNIT	CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT
		FROM	TO								
FAGA131	90606	117.0	118.9	1.9	.9	4A4		4.50	8.70	75.80	
FAGA132	90177	93.2	94.5	1.3	1.3	4L0		.70	1.65		7.20
	90178	133.4	134.9	1.5	1.5	4A4		4.48	10.56	74.70	
FAGA134	90171	65.7	66.4	.7	.7	5B9		1.20	1.40	17.10	
	90172	66.4	67.9	1.5	1.5	4G41		7.56	9.70	99.80	
	92149	163.2	163.7	.5	.5	5D4*		.63	1.68	10.97	
FAGA139	90358	121.1	122.5	1.4	1.1	4L0		.03	.08		1.00
FAGA147	90173	136.2	137.8	1.6	1.6	4L0		.22	.53		3.09
	90174	159.0	160.7	1.7	1.5	5A1		.07	.20		3.09
FAGA151	92026	110.2	112.4	2.2	.0	5D6		.50	.75	8.91	
	92027	112.4	113.4	1.0	.0	4D4		4.15	9.05	80.57	
	92028	113.4	115.2	1.8	.0	4AD		1.80	3.35	33.26	
	92029	122.5	123.4	.9	.0	4AG		1.40	2.65	21.26	
	92030	123.4	124.9	1.5	.0	4A4		3.15	7.42	48.34	
	92031	124.9	126.0	1.1	.0	4A0		.34	.60	6.17	
	92032	129.9	133.2	3.3	.0	3G0		1.70	2.53	24.34	
FAGA153	90161	58.3	60.0	1.7	1.7	4AG		1.18	1.40		15.10
FAGA157	90154	67.6	70.7	3.1	.6	4LEA		1.00	.60		13.00
FAGA161	92079	61.6	63.3	1.7	.5	4AG		.90	1.48	14.74	
FAGA163	90265	43.0	45.4	2.4	.0	4AG		1.20	2.38	16.10	
FAGU001	92150	.0	2.0	2.0	1.8	4A4		3.98	5.89		55.53
	92151	2.0	4.0	2.0	1.8	4A4		4.17	4.60		54.51
	92152	4.0	6.0	2.0	1.9	4A4		4.28	6.45		62.39
	92153	6.0	8.0	2.0	1.9	4A4		4.05	9.45		63.42
	92154	8.0	9.0	1.0	1.0	4A4		4.09	6.90		57.59
	92155	14.0	15.0	1.0	.8	4D4		9.26	15.00		129.24
	92156	15.0	17.3	2.3	1.5	4K4*		3.38	10.46		55.53
	92157	17.3	18.8	1.5	1.4	4K4*		8.50	17.22		111.07
	92158	44.1	45.7	1.6	.2	4E4		8.35	12.52		139.18
	92159	45.7	47.2	1.5	.7	4E4		8.15	14.81		115.87
	92160	47.2	48.8	1.6	1.2	4E4		6.79	13.74		109.01
	92161	48.8	50.3	1.5	1.3	4AE4		7.56	12.16		97.70
	92162	51.8	53.3	1.5	.3	4E4		7.99	10.07		164.89
	92163	53.3	54.9	1.6	.8	4EG4		8.85	14.60		129.24
FAGU003	90144	64.0	65.4	1.4	1.2	4L0		1.00	1.30		15.09
	90145	65.4	66.7	1.3	1.3	4L0		7.04	5.65		88.80
FAGU004	90086	6.9	10.6	3.7	.0	4A24		2.98	4.95	40.50	
	90087	10.6	14.2	3.6	.0	4A24		2.68	4.63	38.40	
	90088	14.2	14.9	.7	.0	4A2		1.13	2.10	19.20	
	90089	14.9	15.5	.6	.0	4A24		2.40	3.80	39.40	
FAGU005	90073	44.2	48.7	4.5	.0	4A14		1.95	3.78	37.80	

DDH	SAMPLE	----DEPTHS----		INT	REC	ROCK UNIT	CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT
		FROM	TO								
FAGU006	90074	.0	2.4	2.4	.4	4A14		2.85	3.65	40.50	
	90075	6.0	9.1	3.1	2.9	4A14		2.28	4.58	34.30	
	90076	14.4	15.2	.8	.8	4A14		.95	2.70	15.40	
	92146	15.2	18.5	3.3	3.3	4A14		1.93	3.65	37.70	
	92147	18.5	19.4	.9	.9	4A14		1.78	3.50	38.70	
FAGU007	90207	10.7	11.2	.5	.0	4A14		3.40	1.53	46.30	
	90208	15.2	19.8	4.6	.4	4A14		2.93	2.43	45.30	
	90209	19.8	21.4	1.6	1.6	4A1		.39	.90	8.90	
	90210	21.4	23.0	1.6	1.5	4A1		.68	1.00	11.00	
	90211	32.0	35.0	3.0	.0	4L24		1.65	2.45		28.50
	90212	35.0	35.7	.7	.0	4L12		3.38	5.09		56.60
	90213	53.8	54.7	.9	.8	4E4		7.39	12.72		128.20
	90214	54.7	56.1	1.4	1.4	4A13		3.00	4.00		44.20
FAGU009	90077	31.0	32.0	1.0	.5	3G46		2.10	2.00		35.30
	90078	32.0	33.0	1.0	1.0	4L4		2.20	2.98		34.30
	90079	38.1	39.5	1.4	.0	3G4		.33	1.10		4.10
FAGU016	90080	60.3	61.1	.8	.8	10Q0		.75	1.05	17.10	
FAGU018	90217	57.6	58.1	.5	.0	4LC		.75	1.05		17.14
	90218	79.9	80.4	.5	.0	4A14		3.30	4.00	45.30	
FAGU022	90219	3.0	4.6	1.6	1.6	4A1		1.63	2.03	24.30	
	90220	10.7	12.2	1.5	1.5	4A1		3.40	1.25	37.40	
	90221	21.3	22.2	.9	.9	4A1		2.20	.93	24.30	
	90222	22.2	22.9	.7	.7	4A14		4.00	2.20	50.40	
FAGU023	90223	.0	1.9	1.9	.6	4A1		2.03	2.55		24.30
	90224	22.3	23.9	1.6	1.5	4A1		1.94	2.50		15.10
	90225	67.1	67.8	.7	.7	4A1		.48	.93	16.10	
FAGU025	90081	59.4	61.0	1.6	1.2	4D0		2.18	3.10	42.51	
	92148	61.0	62.5	1.5	1.2	4CC		.88	2.85	14.06	
FAGU027	90082	94.7	96.0	1.3	.8	4L4		2.23	3.60	33.30	
	90083	99.1	100.6	1.5	1.1	4A1		1.20	2.35	18.20	
	90084	100.6	102.1	1.5	1.1	4A14		2.80	3.30	34.30	
	90085	102.1	103.5	1.4	1.0	4A1		.90	2.33		12.00
FAGU035	90348	51.0	52.1	1.1	1.1	4A96		2.58	5.87		41.50
FAGU036	90587	15.2	16.8	1.6	1.6	4J0		8.17	10.82	133.00	
FAGU037	90588	10.1	10.7	.6	.6	4E4		2.15	5.07	32.20	
	90589	10.7	12.2	1.5	1.5	4E4		2.10	4.98	49.40	
	90590	12.2	13.7	1.5	1.5	4EAG		2.60	5.68	47.30	
	90591	13.7	15.2	1.5	.6	4EG4		4.70	13.68	97.70	
	90592	15.2	16.8	1.6	.4	4E4		4.93	12.76	80.60	
	90593	16.8	18.3	1.5	1.2	4E4		4.80	10.26	86.70	
	90594	18.3	19.8	1.5	1.0	4E4		6.51	13.37	98.70	
	90595	19.8	21.3	1.5	1.5	4E4		6.36	13.12	99.80	
	90596	21.3	22.9	1.6	1.4	4E4		4.65	6.77	80.60	
	90597	22.9	24.4	1.5	1.5	4A31		1.43	1.68	24.30	

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK UNIT	CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT
		FROM	TO								
FAGU037	90598	24.4	25.9	1.5	1.4	4A31		1.18	1.75	24.30	
FAGU038	90937	11.1	12.2	1.1	1.1	4E4		2.35	5.52	33.30	
	90938	12.2	13.7	1.5	1.5	4EA4		1.70	4.13	31.20	
	90939	13.7	15.2	1.5	1.5	4E4		4.63	11.80	76.80	
	90940	15.2	16.8	1.6	.8	4E4		5.63	15.13	85.70	
	90941	16.8	18.3	1.5	1.3	4G0		2.48	6.28	46.30	
	90942	18.3	19.8	1.5	1.4	4G4		3.73	10.77	62.40	
	90943	19.8	21.3	1.5	1.4	4G4		3.45	7.99	60.30	
	90944	21.3	22.9	1.6	1.2	4G4		4.03	9.46	93.90	
	90945	22.9	24.4	1.5	1.5	4EE4		6.20	12.50	104.90	
	90946	24.4	25.9	1.5	1.5	4E4		5.42	10.15	75.80	
	90947	25.9	27.4	1.5	1.5	4AD		4.25	6.02	71.70	
	90948	27.4	29.0	1.6	1.6	4A13		.65	1.18	13.00	
FAGU039	90349	4.1	6.2	2.1	2.1	5C4*		.14	.08	3.10	
FAGU045	90350	61.5	62.5	1.0	.0	4L2					
FAGU073	92080	38.5	39.2	.7	.6	4A4		7.59	17.61	55.54	
	92081	39.2	41.9	2.7	2.7	4A0		.78	1.62	12.00	
FAGU074	92164	56.5	57.9	1.4	1.2	4A134		3.38	3.52		44.23
	92165	57.9	59.2	1.3	1.3	4A13		.85	1.40		13.03
	92166	59.2	60.5	1.3	1.3	4A134		3.33	5.40		35.31
	92167	60.5	61.6	1.1	1.1	4A13		1.72	1.85		23.31
	92168	67.9	69.3	1.4	1.4	4C3		.11	.68		10.97
	92169	69.3	70.6	1.3	1.3	4C3		.12	.45		8.91
	92170	70.6	71.9	1.3	1.3	4C3		.32	1.20		17.14
	92171	71.9	73.1	1.2	1.2	4C3		.70	1.15		6.17
	92172	73.1	74.5	1.4	1.4	4C3		.05	.73		8.23
	92173	74.5	75.7	1.2	1.2	4C3		.80	1.90		30.17
	92174	75.7	77.0	1.3	1.3	4C3		.49	1.73		23.31
	92175	77.0	78.6	1.6	1.4	4C3		.45	1.58		21.26
	92176	78.6	79.9	1.3	1.3	4C3		.48	1.40		16.11
	92177	79.9	81.5	1.6	1.6	4C3		.09	.60		10.97
	92178	81.5	82.8	1.3	1.3	4C3		.49	2.33		15.09
	92179	82.8	84.3	1.5	1.5	4C3		.08	.45		7.20
	92180	84.3	85.6	1.3	1.3	4C3		.07	.68		7.20
	92181	85.6	86.8	1.2	1.2	4C3		.10	.67		8.91
	92182	86.8	88.2	1.4	1.4	4C3		.08	.58		8.91
	92183	88.2	91.4	3.2	3.2	4C3		.50	.75		17.14
	92184	96.8	97.5	.7	.7	4A0		.62	1.00		28.46
	92185	103.1	104.5	1.4	.0	4L124		1.67	2.28		26.40
	92186	104.5	105.9	1.4	.0	4L124		2.25	2.78		34.29
FAGU076	90949	27.4	29.3	1.9	1.5	4E4		3.90	5.00	50.40	
	90950	29.3	30.5	1.2	1.2	4E4		5.15	7.05	83.70	
	90951	30.5	32.0	1.5	1.5	4E4		4.60	5.85	73.70	
	90952	32.0	32.8	.8	.8	4E4		6.92	10.21	86.70	
	90953	32.8	34.3	1.5	1.4	4E4		4.30	5.10	57.60	
	90954	34.3	36.4	2.1	2.0	4D4		12.04	12.77	183.40	
	90955	36.4	38.5	2.1	2.0	4CEA		2.70	1.60	40.50	
	90956	38.5	41.1	2.6	2.5	4A3		1.95	1.15	32.20	
	90957	41.1	42.7	1.6	1.4	4A3		1.20	.25	20.20	

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK UNIT	CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT
		FROM	TO								
FAGU077	92082	163.0	163.7	.7	.7	4LC		1.50	1.78	22.29	
FAGU078	92227	38.1	39.6	1.5	1.4	4A31		.25	1.20		17.14
	92228	44.2	45.7	1.5	1.3	4A31		.05	1.00		9.94
	92229	50.3	51.8	1.5	1.5	4A31		.05	.62		5.14
	92230	56.1	57.6	1.5	1.5	4A10		.40	.42		26.40
	92231	64.0	65.5	1.5	1.5	4A31		.05	.25		4.11
	92232	70.1	71.6	1.5	1.5	4A31		.06	.37		9.94
	92233	77.7	79.2	1.5	1.4	4A31		.14	.75		8.23
	92234	83.8	85.3	1.5	1.5	4A31		.11	.55		18.17
	92235	89.9	91.4	1.5	1.5	4A31		.09	.25		9.94
	92236	94.9	96.5	1.6	1.2	4A31		1.73	2.20		28.46
	92237	96.5	97.8	1.3	1.3	4A31		.66	1.28		20.23
	92238	97.8	99.4	1.6	1.5	4A31		.13	.75		9.94
FAGU080	92187	.0	1.5	1.5	.8	4E15		.82	.35		34.29
	92188	1.5	3.0	1.5	1.4	4AE1		2.45	1.05		52.46
	92189	3.0	4.6	1.6	1.6	4A13		1.98	1.10		50.40
	92190	4.6	5.5	.9	.8	4A13		.80	.59		21.26
	92191	6.4	7.6	1.2	1.2	4C0		.23	4.00		8.91
	92192	7.6	9.1	1.5	1.5	4C0		.40	2.83		15.09
	92193	9.1	10.7	1.6	1.6	4D53		.83	4.70		21.26
	92194	10.7	12.2	1.5	1.5	4D53		2.05	5.00		39.43
	92195	12.2	13.7	1.5	1.4	4D0		1.52	3.88		28.46
	92196	13.7	15.2	1.5	1.2	4DC		1.77	5.65		28.46
	92197	15.2	16.8	1.6	1.2	4DA4		5.20	7.11		72.69
	92198	16.8	18.3	1.5	1.4	4A134		2.40	5.15		37.37
	92199	18.3	19.8	1.5	1.3	4A134		2.10	4.38		34.29
	92200	19.8	21.3	1.5	1.2	4A134		2.10	2.88		30.17
	92201	21.3	22.9	1.6	1.5	4A13		1.00	2.55		16.11
	92202	22.9	24.4	1.5	1.5	4C0		1.29	2.43		21.26
	92203	24.4	25.9	1.5	1.5	4C0		1.04	2.92		19.20
	92204	25.9	27.4	1.5	1.4	4C0		1.05	2.65		17.14
	92205	27.4	29.0	1.6	1.6	4A134		3.35	6.07		50.40
	92206	29.0	30.5	1.5	1.4	4A134		3.30	8.49		56.57
	92207	30.5	32.0	1.5	1.3	4A134		2.50	5.48		39.43
	92208	32.0	33.5	1.5	1.3	4A13		1.45	1.65		22.29
	92209	33.5	35.1	1.6	1.5	4A13		.15	1.18		9.94
	92210	35.1	36.6	1.5	1.3	4A13		.35	1.40		13.03
	92211	36.6	38.1	1.5	.7	4A13		1.14	1.95		22.29
	92212	38.1	39.6	1.5	1.1	4A134		2.65	4.50		37.37
	92213	39.6	41.1	1.5	1.3	4AE4		5.05	9.52		65.49
	92214	41.1	42.7	1.6	1.4	4E4		3.45	5.15		52.46
	92215	42.7	44.2	1.5	1.1	4E4		4.95	2.95		89.83
	92216	44.2	45.7	1.5	1.5	4E4		4.40	8.98		65.49
	92217	45.7	47.2	1.5	1.5	4C3		2.43	2.13		35.31
	92218	47.2	48.8	1.6	1.6	4D3		5.65	4.30		71.66
	92219	48.8	50.3	1.5	1.5	4AE4		2.33	3.80		32.23
	92220	50.3	51.8	1.5	1.5	4AE4		1.45	3.78		26.40
	92221	51.8	53.3	1.5	1.5	4AE4		5.35	5.20		72.69
	92222	53.3	54.9	1.6	1.6	4AE4		2.78	4.90		39.43
	92223	54.9	56.4	1.5	1.5	4AE4		3.05	6.70		50.40
	92224	56.4	57.9	1.5	1.5	4AE4		3.00	6.98		39.43
	92225	57.9	59.4	1.5	1.5	4AE0		1.00	2.53		20.23
	92226	59.4	60.5	1.1	1.1	4AE4		3.43	7.80		55.54

DDH	SAMPLE	----DEPTHS----		INT	REC	ROCK UNIT	CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT
		FROM	TO								
FAGU084	90351	6.3	10.2	3.9	3.5	4L0		.05	.14		.30
	90352	12.4	13.1	.7	.6	4L3		.10	2.10		2.10
	90353	16.7	17.1	.4	.4	4L0		.05	.22		2.10
FAGU086	90226	84.0	85.3	1.3	1.3	4L3		.78	.52		9.90
FAGU088	90228	44.2	45.7	1.5	.0	4E4		5.65	7.90		79.50
	90229	54.6	56.2	1.6	.0	4L34		2.83	4.15	41.50	
FAGU098	90232	.0	2.0	2.0	.0	4E0		4.75	8.61		70.60
	90233	2.0	3.8	1.8	.0	4D4		8.37	19.67		145.00
	90234	3.8	5.8	2.0	.0	4D4		9.17	23.91		152.20
	90235	5.8	8.1	2.3	.0	4LE		2.10	4.65		43.50
	90236	8.1	10.2	2.1	.0	4E4		7.02	9.74		121.00
	90237	10.2	12.6	2.4	.0	4DL		5.46	11.55		76.80
	90238	12.6	14.2	1.6	.0	4EK		3.10	4.05		46.30
	90239	14.2	15.6	1.4	.0	4E4		5.26	7.44		94.60
	90240	15.6	17.1	1.5	.0	4A4		2.68	4.70		45.30
	90241	17.1	18.3	1.2	.0	4AC		1.13	1.78		14.10
	90242	21.5	22.9	1.4	.0	4AG		.68	1.30		9.90
	90243	22.9	23.4	.5	.0	4AG		.73	.75		18.20
	90244	23.4	25.9	2.5	.0	4AC		1.80	2.80		29.10
	90245	25.9	27.4	1.5	.0	4A4		3.78	7.05		46.30
FAGU099	92083	49.2	50.6	1.4	1.4	4EA		4.09	5.78	62.40	
FAGU100	90170	80.2	82.0	1.8	1.6	4A4		2.20	5.20		31.20
	91572	24.4	25.9	1.5	1.5	4A4		2.78	4.55		36.30
FAGU102	90246	27.4	29.0	1.6	.0	4L4		2.58	4.00		44.20
	90247	29.0	33.5	4.5	.0	4L4		2.58	4.40		35.30
	90248	37.9	39.2	1.3	.0	4DL		2.48	6.25	27.40	
FAGU106	90249	15.2	16.8	1.6	.0	4A0		.30	.45		6.20
	90250	97.5	100.0	2.5	.0	4L0		.78	.53		9.90
	90251	125.3	127.5	2.2	.0	5A9		.13	.25		
	90252	127.5	129.9	2.4	.0	5A9		.10	.13		
FAGU107	92084	.0	3.0	3.0	1.2	4DE		1.78	2.60	28.46	
FAGU111	90253	83.4	85.3	1.9	.0	4L12		.10	.30		2.10
	90254	86.8	88.3	1.5	.0	4L2		.38	.25		7.20
	90255	88.3	89.8	1.5	.0	4L21		.05	.03		3.10
	90256	105.8	107.5	1.7	.0	4L		.02	.10		
FAGU113	90257	66.1	66.9	.8	.0	4L0		.74	.64		9.10
FAGU114	90072	22.9	24.4	1.5	1.5	4A4		2.33	3.85	35.30	
FAGU116	90311	5.4	7.1	1.7	.8	5A69		.02	.05	1.03	
	92086	7.1	9.2	2.1	1.4	4L0		.01	.08		
FAGU121	90258	30.5	32.0	1.5	.0	4C0		.38	.78		9.90
	90259	37.8	40.5	2.7	.0	4LC		.28	.50		8.20

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK UNIT	CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT
		FROM	TO								
FAGU135	91064	125.5	128.5	3.0	2.9	4L2		.53	1.00		11.00
	91065	128.5	131.5	3.0	3.0	4LC		.25	.13		5.10
FAGU139	90929	42.7	44.2	1.5	1.5	4EL#		5.97	5.15		82.63
FAGU149	90262	97.4	100.0	2.6	.0	4L72		.73	.68		14.10
FAGU150	90263	92.5	94.5	2.0	.0	4AG		1.53	2.78		23.30
FAGU156	90264	63.9	65.4	1.5	.0	5A6		1.65	2.88		38.40
FAGU185	90607	6.1	7.6	1.5	1.3	4AG		1.23	1.85	20.20	
	90608	7.6	9.1	1.5	1.3	4A34		6.43	14.02	93.90	
	90609	9.1	10.7	1.6	1.6	4A34		6.83	15.27	110.10	
	90610	10.7	12.2	1.5	1.5	4DE4		5.86	11.84	66.50	
	90611	12.2	13.7	1.5	1.5	4E4		7.81	15.99	84.70	
	90612	13.7	15.2	1.5	1.5	4E4		6.43	11.59	84.70	
	90613	15.2	16.8	1.6	1.6	4E4		8.11	17.43	104.90	
	90614	16.8	18.3	1.5	1.5	4D4	10.47	26.45	172.50		
	90615	18.3	19.8	1.5	1.5	4D34	6.23	17.52	90.90		
	90616	19.8	20.5	.7	.7	4D34	9.69	20.65	141.30		
	90617	57.9	58.6	.7	.7	4E46	5.50	9.70	80.60		
FAGU187	91374	16.8	18.3	1.5	1.4	4AG		.10	.70	4.10	
	91375	18.3	19.8	1.5	1.3	4A13		.43	.78	15.10	
	91376	19.8	21.3	1.5	1.3	4A13		1.48	2.65	20.20	
	91377	21.3	22.9	1.6	1.6	4A13		3.05	3.55	40.50	
	91378	22.9	24.4	1.5	1.5	4A13		1.23	1.33	17.10	
	91379	24.4	25.9	1.5	1.4	4A13		1.10	1.48	15.10	
	91380	25.9	27.4	1.5	1.4	4A13		1.93	1.85	20.20	
	91381	27.4	29.0	1.6	1.6	4A13		.98	2.05	31.20	
	91382	29.0	30.5	1.5	1.5	4A13		.60	1.33	8.20	
	91383	30.5	32.0	1.5	.8	4A13	1.63	2.93	22.30		
	91384	32.0	33.5	1.5	1.5	4A13	1.03	1.68	14.10		
	91385	33.5	35.1	1.6	1.6	4A13	.33	1.25	9.90		
	91386	45.7	47.2	1.5	1.5	4D3	.47	4.90	7.20		
	91387	47.2	48.8	1.6	1.6	4C3	.05	1.33	5.10		
	91388	48.8	50.3	1.5	1.5	4C3	.03	.93	5.10		
	91389	50.3	51.8	1.5	1.3	4C3	.04	2.35	9.90		
	91390	51.8	53.3	1.5	.5	4D3	.04	5.00	8.20		
91391	53.3	54.9	1.6	1.4	4C3	.10	2.13	8.90			
91392	54.9	56.4	1.5	1.5	4A0	.09	2.08	12.00			
91393	56.4	57.9	1.5	1.2	4C3	.13	1.95	11.00			
91394	57.9	59.4	1.5	.9	4C3	.28	1.80	8.90			
91395	59.4	60.3	.9	.9	4CE	1.95	3.98	42.50			
FAGU189	90683	56.4	58.4	2.0	1.8	4E4		2.65	5.40	32.20	
	90684	58.4	60.4	2.0	1.3	4A10		1.18	3.40	21.30	
	90685	60.4	61.0	.6	.6	4E0		1.05	1.80	25.40	
	90686	61.0	62.5	1.5	1.5	5D4\$		.18	1.10	3.10	
	90687	82.9	85.3	2.4	2.4	4E0		3.20	1.80	29.10	
	90688	85.3	87.5	2.2	2.0	4E0		1.08	.85	16.10	
	90689	87.5	88.4	.9	.8	4E0		.55	.90	14.10	
	90690	88.4	89.9	1.5	1.5	4E0		1.03	1.43	18.20	
	90691	89.9	90.8	.9	.7	4E0		1.25	1.23	17.10	

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK UNIT	CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT
		FROM	TO								
FAGU189	90692	90.8	93.0	2.2	1.9	4EC		1.85	2.15	27.40	
	90693	93.0	93.9	.9	.2	4CQ		1.05	1.43	12.00	
	90694	93.9	95.4	1.5	1.5	4CQ		.40	.38	8.20	
	90695	95.4	96.3	.9	.5	4CQ		.53	.85	5.10	
	90696	96.3	97.8	1.5	1.5	4CQ		.55	.98	6.20	
	90697	97.8	100.3	2.5	1.6	4CQ		2.78	2.13	24.30	
	90698	100.3	101.8	1.5	1.4	4DC		3.68	2.03	32.20	
	90699	101.8	103.6	1.8	1.7	4CQ		1.85	1.20	20.20	
	90700	103.6	105.2	1.6	1.6	4DC		2.48	2.63	29.10	
	90701	105.2	106.7	1.5	1.5	4DC		4.45	4.95	67.50	
	90702	106.7	108.2	1.5	1.5	4CQ		1.53	1.13	25.40	
	90703	108.2	109.7	1.5	1.5	4EC		1.03	.83	15.10	
	90704	112.8	114.3	1.5	1.5	4CQ		2.03	2.65	36.30	
	FAGU191	90618	6.1	9.1	3.0	2.3	4A13		.45	.80	9.90
90619		9.1	12.2	3.1	3.0	4A13		.60	1.30	25.40	
90620		12.2	13.7	1.5	1.4	4A13		3.35	3.75	50.40	
90621		13.7	15.2	1.5	1.5	4DE4		7.15	12.83	94.60	
90622		15.2	16.8	1.6	1.6	4EA		5.00	9.60	83.70	
90623		16.8	18.3	1.5	1.4	4E4		6.62	12.28	86.70	
90624		18.3	19.8	1.5	1.1	4ED4		6.85	13.69	103.90	
90625		19.8	21.3	1.5	1.1	4D45		8.96	14.71	126.20	
90626		21.3	24.3	3.0	1.7	4DE4		6.95	12.53	109.00	
90627		50.3	53.3	3.0	1.2	4E4		5.33	15.46	75.80	
90628		53.3	56.4	3.1	1.1	4EC		4.40	13.20	67.50	
90629		56.4	57.9	1.5	.9	4E4		7.05	16.45	114.20	
FAGU192		90799	.0	1.9	1.9	1.1	4A4		2.13	4.10	27.40
	90800	1.9	3.8	1.9	1.7	4A4		2.93	2.70	35.30	
	90801	3.8	5.3	1.5	1.4	4CQ		.85	1.18	9.90	
	90802	5.3	6.8	1.5	1.5	4CQ		1.93	2.50	22.30	
	90803	6.8	8.3	1.5	1.5	4CQ		1.10	1.05	13.00	
	90804	8.3	9.8	1.5	1.5	4CQ		.95	1.43	9.90	
	90805	9.8	12.8	3.0	3.0	4CQ		1.03	1.48	13.00	
	90806	15.0	16.5	1.5	1.4	4DC		2.48	3.25	35.30	
	90807	16.5	18.0	1.5	1.5	4CC		1.93	2.80	22.30	
	90808	18.0	19.5	1.5	1.5	4CQ		1.50	2.00	17.10	
	90809	19.5	21.0	1.5	.0	4CQ		2.05	2.93	24.30	
	90810	21.0	22.5	1.5	1.5	4CQ		2.08	2.85	25.40	
	90811	60.7	63.7	3.0	2.8	4AG		.35	.83	8.90	
	90812	63.7	66.7	3.0	2.6	4AG		1.38	2.20	22.30	
	90813	66.7	69.0	2.3	2.0	4AG		.03	.43	7.20	
	90814	69.0	70.5	1.5	1.5	4E4		3.93	5.25	65.50	
	90815	70.5	72.0	1.5	1.5	4EG4		3.18	7.78	57.60	
	90816	72.0	73.5	1.5	1.5	4E46		4.50	8.24	65.50	
	90817	73.5	75.0	1.5	1.5	4E46		2.63	4.60	33.30	
	90818	75.0	76.5	1.5	1.5	4E60		1.13	3.18	17.10	
90819	76.5	78.0	1.5	1.5	4EG0		1.10	2.93	12.00		
90820	78.0	79.5	1.5	1.5	4EG		3.23	6.01	50.40		
90821	79.5	81.0	1.5	1.5	4EG4		5.85	11.16	85.70		
90822	81.0	82.5	1.5	1.5	4E4		4.65	3.35	50.40		
90823	82.5	84.0	1.5	1.5	4E0		2.20	1.75	29.10		
90824	84.0	85.5	1.5	1.5	4E4		3.28	4.40	51.40		
90825	85.5	87.0	1.5	1.2	4E4		4.08	6.25	62.40		
90826	87.0	88.5	1.5	1.3	4L4		1.05	2.13	15.10		

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK UNIT	CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT
		FROM	TO								
FAGU192	90827	88.5	90.0	1.5	1.5	4E46		4.78	7.17	62.40	
	90828	90.0	91.5	1.5	1.4	4E46		3.90	7.88	60.30	
	90829	91.5	93.0	1.5	1.3	4AG		.88	1.30	16.10	
	90830	93.0	94.5	1.5	1.5	4E4		4.05	7.73	60.30	
	90831	94.5	96.0	1.5	1.5	4A4		3.00	4.60	44.20	
	90832	96.0	97.5	1.5	1.5	4EA4		2.75	5.56	40.50	
	90833	97.5	99.0	1.5	1.5	4AG		.93	1.43	29.10	
	90834	99.0	100.5	1.5	1.5	4AG		3.00	6.54	51.40	
	90835	100.5	102.0	1.5	1.5	4A34		4.03	7.42	62.40	
	90836	102.0	103.5	1.5	1.5	4A4		2.05	3.68	32.20	
	90837	103.5	105.0	1.5	1.5	4A4		4.70	4.70	61.40	
	90838	105.0	106.5	1.5	1.5	4A31		.45	.33	16.10	
	90839	106.5	108.0	1.5	1.5	4AC3		.08	1.38	8.20	
	90840	108.0	109.5	1.5	1.5	4A1		.13	1.15	11.00	
	90841	109.5	111.0	1.5	1.5	4A1		.10	.30	9.90	
	90842	111.0	112.5	1.5	1.5	4A1		.08	.25	13.00	
	90843	112.5	114.0	1.5	1.5	4A1		.08	.53	12.00	
90844	114.0	115.5	1.5	1.5	4C30		.15	1.03	12.00		
90845	115.5	117.3	1.8	1.5	4C30		.43	1.30	16.10		
FAGU193	90630	36.5	38.1	1.6	1.6	4EG4		7.55	10.60	100.80	
	90631	38.1	39.6	1.5	1.5	4G4		4.10	9.75	50.40	
	90632	39.6	41.1	1.5	1.4	4GA4		6.55	10.21	78.90	
	90633	41.1	42.7	1.6	1.6	4A4		6.25	9.20	98.70	
FAGU194	90846	1.2	4.0	2.8	2.3	4A4		2.35	3.00	28.50	
	90847	4.0	5.5	1.5	1.5	4C0		1.55	.93	19.20	
	90848	5.5	7.0	1.5	1.4	4C0		1.03	1.40	11.00	
	90849	7.0	8.5	1.5	1.5	4D0		1.98	3.10	27.40	
	90850	8.5	10.0	1.5	1.5	4C0		.90	1.80	9.90	
	90851	10.0	11.5	1.5	1.4	4C0		1.28	1.60	12.00	
	90852	11.5	13.0	1.5	1.5	4C0		.93	1.30	8.90	
	90853	13.0	14.5	1.5	1.3	4C0		.95	.63	11.00	
	90854	14.5	17.5	3.0	2.7	4AG		2.33	2.55	33.30	
	90855	17.5	19.8	2.3	2.3	4AG		2.05	2.75	28.50	
	90856	39.5	41.0	1.5	1.5	4AG		.40	1.00	8.20	
	90857	41.0	42.5	1.5	1.4	4AG		1.08	2.28	20.20	
	90858	42.5	44.0	1.5	1.4	4AG		.53	1.13	12.00	
	90859	44.0	45.5	1.5	1.5	4AG		.23	.78	6.20	
	90860	45.5	47.0	1.5	1.5	4AC0		.23	.73	7.20	
	90861	47.0	48.5	1.5	1.5	4AG		.13	.43	7.20	
	90862	48.5	50.0	1.5	1.3	4A13		1.90	3.90	34.30	
	90863	50.0	51.5	1.5	1.5	4A13		3.65	7.20	68.60	
	90864	51.5	53.4	1.9	1.7	4EC		3.23	5.82	59.30	
	90865	57.2	58.7	1.5	1.4	4C\$3		3.00	4.25	58.60	
	90866	58.7	60.2	1.5	1.5	4E4		8.97	11.07	114.90	
	90867	60.2	61.7	1.5	1.3	4G4		4.23	7.93	96.70	
	90868	61.7	63.2	1.5	1.4	4Q*		3.28	5.48	58.60	
	90869	63.2	64.7	1.5	1.5	4EG		3.38	5.71	48.30	
	90870	64.7	66.2	1.5	1.5	4E4		4.90	6.57	81.60	
	90871	66.2	67.7	1.5	1.4	4EG		3.20	6.90	80.60	
	90872	67.7	69.2	1.5	1.4	4E4		4.13	9.21	74.70	
90873	69.2	70.7	1.5	1.3	4E4		5.00	8.26	84.70		
90874	70.7	72.2	1.5	1.5	4E4		3.93	4.00	57.60		
90875	72.2	73.7	1.5	1.2	4E0		2.70	1.50	43.50		

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK UNIT	CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT
		FROM	TO								
FAGU194	90876	73.7	75.2	1.5	1.5	4E4		4.94	5.91	78.90	
	90877	75.2	76.2	1.0	1.0	4E4		3.90	5.05	78.90	
	90878	87.2	88.7	1.5	1.5	4A4		9.71	18.19	147.10	
	90879	88.7	90.2	1.5	1.5	4E14		6.99	14.00	104.90	
	90880	90.2	91.7	1.5	1.5	4E14		5.23	8.04	79.50	
	90881	91.7	93.2	1.5	1.5	4EC		2.73	5.05	43.50	
	90882	93.2	94.7	1.5	1.5	4C3		.55	1.05	15.10	
	90883	94.7	96.2	1.5	1.5	4C3		.88	1.93	17.10	
	90884	96.2	97.7	1.5	1.5	4D3		4.25	6.19	63.40	
	90885	97.7	99.2	1.5	1.5	4C3		1.00	2.48	21.30	
	90886	99.2	100.7	1.5	1.5	4C3		1.43	2.98	26.40	
	90887	100.7	102.2	1.5	1.5	4C35		1.05	1.28	25.40	
	90888	102.2	103.7	1.5	1.5	4C35		.13	.65	18.20	
	90889	103.7	105.2	1.5	1.5	4C3		.48	.50	18.20	
	90890	105.2	106.7	1.5	1.5	4D3		2.28	2.80	37.40	
	90891	106.7	108.2	1.5	1.5	4D3		3.88	5.00	60.30	
	90892	108.2	109.7	1.5	1.5	4C3		.70	1.63	25.40	
90893	109.7	111.4	1.7	1.5	4C3		2.08	1.93	34.30		
FAGU195	90634	16.8	18.3	1.5	1.2	4E4		3.95	10.08	57.60	
	90635	18.3	19.8	1.5	1.4	4E4		4.33	11.32	59.30	
	90636	19.8	21.3	1.5	1.4	4E4		5.80	12.98	91.90	
	90637	21.3	22.9	1.6	1.5	4E4		6.92	15.01	108.00	
	90638	22.9	24.4	1.5	1.5	4E4		3.40	7.80	50.40	
	90639	24.4	25.9	1.5	1.3	4D4		7.67	14.91	114.90	
	90640	25.9	27.4	1.5	1.5	4E4		7.94	17.86	114.90	
	90641	27.4	29.0	1.6	1.0	4E4		6.95	14.29	96.70	
	90642	29.0	30.5	1.5	1.2	4A13		6.15	7.99	84.70	
	90643	30.5	33.5	3.0	1.0	4A13		.05	.13	6.17	
FAGU196	90644	.0	3.0	3.0	1.6	4A0		1.80	1.70	20.20	
	90645	3.0	4.5	1.5	1.4	4A0		1.95	2.93	26.40	
	90646	4.5	6.0	1.5	1.3	4A0		1.63	1.63	22.30	
	90647	6.0	7.5	1.5	1.5	4C0		1.60	.88	22.30	
	90648	7.5	9.0	1.5	1.4	4C0		.88	.35	12.00	
	90649	9.0	10.5	1.5	1.3	4A0		2.20	2.00	32.20	
	90650	10.5	12.0	1.5	1.3	4A4		2.88	2.55	36.30	
	90651	12.0	13.5	1.5	1.3	4A4		2.70	2.95	32.20	
	90652	13.5	15.0	1.5	1.2	4A0		2.80	1.25	30.20	
	90653	15.0	16.5	1.5	1.5	4AC		3.10	1.85	31.20	
	90654	16.5	18.0	1.5	1.3	4A0		2.70	.80	26.40	
	90655	18.0	19.5	1.5	1.5	4A0		.13	.55	3.10	
	90656	19.5	21.0	1.5	1.5	4A0		.10	.10	6.20	
	90657	21.0	22.5	1.5	1.5	4A0		.14	.35	6.20	
	90658	22.5	25.5	3.0	2.7	4A0		.75	.73	8.90	
	90659	25.5	28.5	3.0	2.8	4A0		.18	.40	3.10	
	90660	28.5	31.5	3.0	2.8	4A0		.13	.93	3.10	
	90661	31.5	34.5	3.0	3.0	4A0		.53	1.23	8.90	
	90662	34.5	36.6	2.1	2.0	4A4		1.95	3.40	30.20	
90663	36.6	38.1	1.5	1.5	4AE		2.58	4.15	41.50		
90664	38.1	39.6	1.5	1.5	4E4		6.23	8.77	92.90		
90665	39.6	40.3	.7	.7	4E4		6.10	8.47	102.90		
90666	62.5	64.0	1.5	1.5	4EG		5.00	8.21	93.90		
90667	64.0	65.5	1.5	1.5	4EG		6.85	5.10	184.50		
90668	65.5	67.0	1.5	1.5	4G4		5.70	8.06	108.00		

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK UNIT	CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT	
		FROM	TO									
FAGU196	90669	67.0	68.5	1.5	1.5	4EG		4.00	6.80	69.60		
	90670	68.5	70.0	1.5	1.5	4EG4		5.00	8.49	82.60		
	90671	70.0	71.5	1.5	1.5	4EG4		4.35	7.50	76.80		
	90672	94.5	96.0	1.5	.5	4J4		4.28	19.19	61.40		
	90673	96.0	97.5	1.5	1.2	4J4		9.02	20.34	150.20		
	90674	97.5	99.0	1.5	1.3	3GG		2.53	5.65	42.50		
	90675	99.0	100.5	1.5	1.3	4E4		2.03	4.55	36.30		
	90676	100.5	102.0	1.5	1.3	4E4		4.65	8.31	70.60		
	90677	102.0	103.5	1.5	1.2	4E10		1.05	3.68	25.40		
	90678	103.5	105.0	1.5	1.4	4E4		2.23	3.15	39.40		
	90679	105.0	106.5	1.5	1.3	4E4		1.63	4.03	30.20		
	90680	106.5	108.0	1.5	1.1	4CG		1.20	3.18	25.40		
	90681	108.0	109.5	1.5	.9	4DG		2.58	2.75	45.30		
	90682	109.5	111.0	1.5	.5	4DG		3.25	4.85	48.30		
FAGU198	90705	45.7	47.2	1.5	1.5	4BE		2.20	1.15	39.40		
	90706	47.2	49.0	1.8	1.8	4EQ		2.88	1.85	42.50		
	90707	90.5	92.0	1.5	1.5	4E46		5.76	8.04	101.80		
	90708	92.0	93.5	1.5	1.5	4E46		6.65	9.70	123.10		
	90709	93.5	94.7	1.2	1.2	4E46		5.44	9.70	91.90		
	90710	134.1	135.6	1.5	1.5	4EA4		2.88	2.85	36.30		
	90711	135.6	137.1	1.5	1.5	4A1		.88	.88	13.00		
	90712	137.1	138.6	1.5	1.5	4A1		.08	.10	4.10		
	90713	146.9	148.4	1.5	1.5	4A1		1.28	1.50	20.20		
	90714	148.4	149.9	1.5	1.3	4A1		.18	.70	7.20		
	90715	149.9	151.4	1.5	1.5	4A1		1.18	1.33	23.30		
	FAGU199	90716	2.1	3.6	1.5	.9	4E4		8.39	12.65	124.10	
		90717	3.6	5.1	1.5	1.3	4EG4		7.40	10.21	114.20	
		90718	5.1	6.6	1.5	1.4	4G4		6.40	8.85	92.90	
90719		6.6	8.1	1.5	1.5	4G4		7.85	10.31	113.10		
90720		8.1	9.6	1.5	1.2	4G4		6.50	8.95	75.80		
90721		9.6	11.1	1.5	1.0	4G4		6.75	10.15	76.80		
90722		11.1	12.6	1.5	1.0	4E4		6.97	8.69	104.90		
90723		12.6	14.1	1.5	1.0	5C4*		3.60	8.16	46.30		
90724		14.1	15.6	1.5	.8	4A10		3.03	3.35	47.30		
90725		15.6	17.1	1.5	1.3	4AE4		6.75	6.52	97.70		
90726		17.1	18.6	1.5	1.4	4G4		8.60	11.52	156.30		
90727		18.6	20.1	1.5	1.2	4G4		7.40	9.93	114.20		
90728		20.1	21.6	1.5	1.4	4G4		7.00	9.70	93.90		
90729		21.6	23.1	1.5	.9	4G4		7.20	9.65	101.80		
90730		23.1	24.6	1.5	.8	4G4		4.18	6.31	79.50		
90731		27.0	28.5	1.5	1.5	4G4		6.10	10.21	108.00		
90732		28.5	30.0	1.5	1.4	4G4		5.40	9.55	98.70		
90733		30.0	31.5	1.5	1.5	4G4		6.20	9.85	139.20		
90734		31.5	33.0	1.5	1.5	4G4		6.40	9.25	104.90		
90735		33.0	34.5	1.5	1.3	4G4		5.10	9.78	85.70		
90736	34.5	36.0	1.5	1.1	4EG4		4.55	9.18	62.40			
90737	103.0	104.5	1.5	1.4	4E4		3.90	3.65	49.40			
90738	104.5	106.0	1.5	1.5	4EG		1.83	1.05	29.10			
90739	106.0	107.5	1.5	1.1	4K0		1.13	.30	27.40			
90740	107.5	109.0	1.5	1.5	4E4		6.80	6.47	68.60			
90741	109.0	110.5	1.5	1.3	4E0		1.95	1.73	23.30			
FAGU200	90742	6.0	7.9	1.9	1.2	4E4		7.95	15.80	126.20		

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK UNIT	CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT
		FROM	TO								
FAGU200	90743	7.9	9.4	1.5	1.1	4E4		9.17	16.40	138.20	
	90744	9.4	10.9	1.5	.9	4E4		8.88	14.23	122.10	
	90745	10.9	12.4	1.5	1.3	4E4		9.94	11.45	147.10	
	90746	12.4	13.9	1.5	.9	4E4		6.30	10.43	100.80	
	90747	13.9	15.4	1.5	.9	5A6		.88	2.38	16.10	
	90748	15.4	16.9	1.5	1.1	4E4		6.63	11.55	110.10	
	90749	16.9	18.4	1.5	1.0	4E4		9.52	15.70	162.50	
	90750	18.4	20.0	1.6	1.0	4E4		8.63	14.68	117.30	
	90751	21.3	22.9	1.6	1.5	4A0		2.33	1.10	31.20	
	90752	22.9	24.4	1.5	1.5	4A4		2.50	4.30	43.50	
	90753	24.4	27.0	2.6	1.4	4A4		2.05	3.45	30.20	
	FAGU204	90754	19.8	21.3	1.5	1.3	4E4		7.32	12.90	102.90
90755		21.3	22.9	1.6	1.2	4E4		6.48	13.51	89.80	
90756		22.9	24.4	1.5	1.5	4EK4		2.33	8.26	59.30	
90757		24.4	25.9	1.5	.9	4E4		3.45	9.60	49.00	
90758		25.9	27.4	1.5	1.4	4E4		5.51	9.37	72.70	
90759		27.4	29.0	1.6	1.4	4E4		11.45	17.33	150.20	
90760		29.0	30.7	1.7	1.6	4E4		7.25	10.67	114.20	
90761		30.7	32.2	1.5	1.3	4A1		1.60	2.90	26.40	
FAGU206		90894	1.5	3.0	1.5	1.4	4A4		4.35	8.98	66.50
	90895	3.0	4.6	1.6	1.4	4A34		3.45	4.60	45.30	
	90896	4.6	6.1	1.5	1.5	4A34		5.70	4.00	67.50	
	90897	6.1	7.6	1.5	1.3	4D54		9.75	6.33	114.20	
	90898	7.6	9.1	1.5	1.4	4D5		4.78	4.25	58.60	
	90899	9.1	12.2	3.1	3.1	4D5		3.65	4.20	43.50	
	90900	12.2	13.7	1.5	1.5	4A43		6.50	2.50	69.60	
	90901	13.7	15.2	1.5	1.5	4A43		8.50	4.40	89.80	
	90902	15.2	16.8	1.6	1.5	4A43		4.03	2.03	46.30	
	90903	16.8	18.3	1.5	1.5	4A43		5.04	2.33	55.50	
	90904	18.3	19.8	1.5	1.5	4A43		4.85	1.63	55.50	
	90905	19.8	21.3	1.5	1.5	4A43		5.70	1.48	64.50	
	90906	21.3	22.9	1.6	1.6	4A34		8.55	7.52	83.70	
	90907	22.9	24.4	1.5	1.5	4A34		3.70	2.70	41.50	
	90908	24.4	25.9	1.5	1.5	4A34		3.33	4.10	47.30	
	90909	25.9	27.4	1.5	1.2	4D0		2.15	4.66	37.40	
	90910	27.4	29.0	1.6	1.5	4D0		2.38	5.00	44.20	
	90911	29.0	30.5	1.5	1.4	4A4		2.15	4.76	40.50	
	90912	30.5	32.0	1.5	1.5	4A4		1.90	3.95	39.40	
	90913	32.0	33.5	1.5	1.5	4A4		1.60	3.73	33.30	
	90914	33.5	35.1	1.6	1.6	4A4		1.90	4.68	39.40	
	90915	35.1	36.6	1.5	1.5	4A0		1.75	2.53	31.20	
	90916	36.6	38.1	1.5	1.5	4A4		3.35	6.48	57.60	
	90917	38.1	39.6	1.5	1.5	4A4		2.48	4.06	46.30	
	90918	39.6	41.1	1.5	1.5	4A4		3.30	7.44	66.50	
	90919	41.1	42.7	1.6	1.5	4D5		1.80	3.30	29.10	
	90920	42.7	44.2	1.5	1.5	4C5		1.15	1.40	15.10	
90921	44.2	45.7	1.5	1.5	4C5		1.40	2.88	23.30		
90922	45.7	47.2	1.5	1.5	4A0		1.38	3.25	26.40		
90923	47.2	48.8	1.6	1.6	4A4		1.68	4.18	30.20		
90924	48.8	50.3	1.5	1.4	4A0		1.43	3.18	21.30		
90925	50.3	51.8	1.5	1.5	4A0		1.50	3.00	24.30		
90926	51.8	53.3	1.5	.8	4A4		1.58	4.20	27.40		
90927	53.3	54.9	1.6	.8	4A0		1.70	2.48	26.40		

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK UNIT	CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT
		FROM	TO								
FAGU206	90928	54.9	56.4	1.5	.5	4EC		.63	1.30	11.00	
	90930	57.9	59.4	1.5	.8	4A10		1.83	2.40	24.30	
	90931	59.4	61.0	1.6	1.6	4CD5		2.20	5.50	30.20	
	90932	61.0	62.5	1.5	.5	4A0		1.35	2.88	21.30	
	90933	62.5	64.0	1.5	1.5	4A34		5.42	7.70	67.50	
	90934	64.0	65.5	1.5	.9	4A34		6.65	10.55	80.60	
	90935	65.5	67.1	1.6	1.4	4A34		7.61	11.66	102.90	
	90936	67.1	68.5	1.4	.5	4E4		9.89	16.00	138.20	
FAGU207	90762	.0	4.6	4.6	1.5	4A43		4.80	8.78	82.60	
	90763	4.6	6.1	1.5	1.4	4A43		4.10	7.87	63.40	
	90764	7.6	9.1	1.5	1.2	4A43		3.00	6.67	59.30	
	90765	9.1	10.6	1.5	1.5	4A43		2.15	4.00	38.40	
	90766	10.6	12.1	1.5	1.5	4A43		3.10	4.56	54.50	
	90767	12.1	13.6	1.5	1.5	4A43		2.95	5.56	52.50	
	90768	13.6	15.1	1.5	1.2	4A43		3.00	5.00	45.30	
	90769	15.1	16.7	1.6	1.0	4A43		2.90	7.98	43.50	
	90770	16.7	18.2	1.5	1.0	4A43		2.68	3.90	35.30	
	90771	18.2	20.4	2.2	2.1	4A43		3.90	8.48	59.30	
FAGU208	91396	.0	1.5	1.5	.6	4D4		6.52	8.88	75.80	
	91397	1.5	3.0	1.5	1.5	4D4		3.58	7.32	55.50	
	91398	3.0	4.6	1.6	1.5	4D4		4.60	6.87	60.30	
	91399	4.6	6.1	1.5	1.5	4D4		4.25	8.78	66.50	
	91400	6.1	7.5	1.4	1.3	4AD4		2.80	7.47	47.30	
	91401	8.5	9.9	1.4	1.3	4EKD		5.00	11.10	68.60	
	91402	45.7	47.2	1.5	1.3	4ED4		4.98	6.16	74.70	
	91403	47.2	48.8	1.6	1.0	4E4		8.50	15.65	112.10	
	91404	48.8	50.3	1.5	1.5	4G4		4.90	8.98	85.70	
	91405	50.3	51.8	1.5	1.5	4G4		5.75	8.13	90.90	
	91406	51.8	53.3	1.5	1.5	4E4		4.28	4.55	63.40	
	91407	53.3	55.5	2.2	2.2	4G4		4.65	7.12	81.60	
	91408	55.5	57.1	1.6	1.6	4A0		1.53	2.68	25.40	
	91409	129.8	131.1	1.3	1.3	4E4		3.25	3.20	41.50	
	91410	131.1	132.6	1.5	1.5	4EC		1.93	.75	19.20	
	91411	132.6	134.1	1.5	1.5	4G4		4.38	5.68	65.50	
	91412	134.1	135.6	1.5	1.5	4C8		.58	.93	14.10	
	91413	135.6	137.2	1.6	1.6	4C8		.33	.50	8.90	
	91414	137.2	138.7	1.5	1.5	4C8		.63	.45	9.90	
	91415	138.7	140.2	1.5	1.5	4C8		.65	1.63	9.90	
91570	33.0	34.0	1.0	.9	3G0		1.85	4.88	27.40		
FAGU209	91416	.0	3.0	3.0	1.4	4D3		4.90	3.55	48.50	
	91417	3.0	4.5	1.5	1.5	4D3		4.28	3.08	49.40	
	91418	4.5	6.0	1.5	1.5	4D34		4.45	9.52	66.50	
	91419	6.0	7.5	1.5	.8	4A4		1.68	5.45	27.40	
	91420	7.5	9.0	1.5	.7	4A4		2.55	5.73	39.40	
	91421	9.0	10.5	1.5	1.3	4EDK		6.98	10.80	122.10	
	91422	13.8	16.8	3.0	1.7	4D4\$		5.33	10.49	89.80	
	91423	16.8	18.3	1.5	1.4	4E4\$		6.04	13.42	93.90	
	91424	18.3	19.8	1.5	.6	4EDL		3.55	8.91	53.50	
	91425	21.3	22.8	1.5	1.4	4D4\$		5.53	9.01	78.90	
	91426	22.8	24.3	1.5	1.5	4D4		6.98	13.58	102.90	
	91427	24.3	26.0	1.7	1.6	4ED		10.25	19.77	217.40	
	91428	33.5	35.1	1.6	1.5	4D4\$		4.70	6.92	65.50	

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK UNIT	CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT
		FROM	TO								
FAGU209	91429	39.4	41.1	1.7	1.6	4DL		3.90	4.55	52.50	
	91430	41.1	42.7	1.6	1.5	4DL		2.78	2.90	40.50	
	91431	42.7	44.2	1.5	.7	4E4*		6.23	10.29	131.00	
	91432	44.2	45.7	1.5	1.1	4E4*		5.67	8.75	97.70	
	91433	45.7	47.2	1.5	1.0	4E4*		6.49	10.25	108.00	
	91434	47.2	48.7	1.5	.9	4E4*		4.55	6.41	69.60	
	91435	48.7	50.2	1.5	.8	4E4*		3.48	5.30	48.30	
	91436	50.2	51.9	1.7	1.0	4AC		1.05	1.90	16.10	
	91571	57.9	59.4	1.5	.0	4AC		1.98	2.63	22.30	
FAGU210	91437	.0	3.0	3.0	.7	4D54		6.42	4.55	71.70	
	91438	3.0	4.5	1.5	1.3	5D4*		.85	2.70	14.10	
	91439	4.5	6.0	1.5	1.2	4D4		3.73	8.11	56.60	
	91440	6.0	7.5	1.5	1.5	4D4		3.70	7.90	53.50	
	91441	7.5	9.0	1.5	.8	5D4*		2.30	4.80	33.30	
	91442	9.0	10.5	1.5	1.4	4D45		3.78	6.90	58.60	
	91443	10.5	12.0	1.5	1.1	4D5		3.20	6.55	46.30	
	91444	12.0	13.5	1.5	1.1	5D4*		2.90	5.30	48.30	
	91445	13.5	15.0	1.5	1.5	4D45		3.82	9.05	68.60	
	91446	15.0	16.5	1.5	1.3	4D45		4.13	9.01	78.90	
	91447	16.5	18.0	1.5	1.1	4C5		1.38	3.13	23.30	
	91448	18.0	19.5	1.5	.9	4D5		2.88	6.92	50.40	
	91449	19.5	21.0	1.5	1.5	4D45		7.83	13.57	125.10	
	91450	21.0	22.5	1.5	1.5	4D45		5.00	9.74	80.60	
	91451	22.5	24.0	1.5	1.5	4A4		2.63	5.63	42.50	
	91452	24.0	25.5	1.5	1.5	5D4*		.53	.25	8.20	
	91453	25.5	27.1	1.6	1.5	4A3		1.75	1.48	27.40	
	91454	29.8	32.0	2.2	2.2	4E4\$		7.68	16.70	140.20	
	91455	36.4	38.4	2.0	1.8	4A4		6.19	7.87	79.50	
	91456	59.4	60.9	1.5	1.5	4LDE		6.22	9.59	88.80	
	91457	60.9	62.4	1.5	1.5	4E4		4.87	7.52	71.70	
	91458	62.4	63.9	1.5	1.5	4E4		5.00	7.70	69.60	
	91459	63.9	65.4	1.5	1.5	4AE		5.63	10.60	81.60	
	91460	65.4	66.9	1.5	1.1	4AC		1.13	1.45	15.10	
	91461	89.9	92.9	3.0	1.7	4AG		.58	.73	13.00	
	91462	92.9	94.4	1.5	1.5	4A0		.18	.65	14.10	
	91463	94.4	95.9	1.5	1.1	4AC		.15	.28	8.20	
91464	95.9	98.9	3.0	2.1	4A0		.33	1.08	8.20		
91465	98.9	100.4	1.5	1.5	4AG		.73	1.35	13.00		
91466	100.4	101.9	1.5	1.3	4A0		.05	.45	3.10		
91467	101.9	104.9	3.0	2.2	4AG		.05	.33	5.10		
91468	104.9	107.9	3.0	2.9	4A0		.07	1.05	4.10		
91469	107.9	109.9	2.0	2.0	4EC		1.00	1.63	23.30		
91470	113.2	114.4	1.2	1.2	4D45		6.99	12.52	98.70		
FAGU211	91471	1.2	4.6	3.4	1.1	4AC		1.58	2.55	22.30	
	91472	4.6	7.6	3.0	1.6	4C5		1.13	.88	14.10	
	91473	7.6	9.1	1.5	1.3	4C5		1.68	1.53	20.20	
	91474	9.1	10.6	1.5	1.1	4C5		1.03	1.83	14.10	
	91475	10.6	13.6	3.0	.9	4C5		.90	.93	9.90	
	91476	13.6	16.6	3.0	1.2	4AC		1.53	.75	19.20	
	91477	16.6	19.6	3.0	1.1	4A4		4.50	6.55	59.30	
	91478	19.6	21.1	1.5	1.0	4A4		1.90	3.35	26.40	
	91479	21.1	22.6	1.5	.9	4A4		3.58	7.48	45.30	
	91480	22.6	24.1	1.5	.8	4A4		3.93	7.54	51.40	

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK UNIT	CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT
		FROM	TO								
FAGU211	91481	24.1	25.9	1.8	.8	4AC		1.08	2.95	18.20	
	91482	25.9	27.4	1.5	1.5	4E4		8.99	15.07	159.40	
	91483	27.4	28.1	.7	.7	4E4		6.43	9.22	110.10	
	91484	35.4	36.9	1.5	1.5	4AEG		2.63	4.85	59.30	
	91485	36.9	38.4	1.5	1.5	4G4		4.48	8.19	69.60	
	91486	38.4	39.5	1.1	1.1	4G4		3.40	7.16	72.70	
	91487	39.5	41.0	1.5	1.5	4G4		4.50	7.24	75.80	
	91488	41.0	42.5	1.5	1.5	4G4		5.00	7.87	74.70	
	91489	42.5	44.3	1.8	1.7	4E4		2.85	3.20	60.30	
	91490	71.6	73.1	1.5	1.5	4D4		4.33	6.44	64.50	
	91491	73.1	74.6	1.5	1.5	4C3		1.80	2.15	33.30	
	91492	74.6	76.1	1.5	1.4	4D53		2.68	4.75	42.50	
	91493	76.1	77.6	1.5	1.5	4D53		2.73	2.60	46.30	
	91494	77.6	79.1	1.5	1.5	4C3		.25	.53	11.00	
	91495	79.1	80.6	1.5	1.4	4C3		.40	.80	15.10	
	91496	80.6	82.1	1.5	1.4	4C3		.05	.55	9.90	
	91497	82.1	83.6	1.5	1.5	4C3		.30	.65	13.00	
	91498	83.6	85.1	1.5	1.5	4C3		.25	.65	12.00	
	91499	85.1	86.6	1.5	1.5	4C3		.80	2.00	24.30	
	91500	86.6	88.1	1.5	1.5	4D4		5.56	6.56	73.70	
FAGU212	91501	10.7	11.2	.5	.5	4AG		1.30	2.73	15.10	
	91502	11.2	12.2	1.0	1.0	4C5		1.48	1.93	19.20	
	91503	12.2	13.7	1.5	1.5	4C0		2.15	1.60	24.30	
	91504	13.7	15.2	1.5	1.3	4D0		3.40	3.00	40.50	
	91505	15.2	16.8	1.6	1.5	4D0		2.60	3.55	32.20	
	91506	16.8	18.3	1.5	1.2	4C0		2.23	2.75	28.50	
	91507	18.3	19.8	1.5	1.5	4C0		1.68	2.65	20.20	
	91508	19.8	21.3	1.5	1.5	4C0		.40	.63	5.10	
	91509	21.3	22.9	1.6	1.0	4C0		1.48	2.00	20.20	
	91510	30.0	32.0	2.0	2.0	4C0		.50	.78	8.20	
	91511	32.0	33.5	1.5	1.5	4A0		.33	1.18	6.20	
	91512	33.5	36.0	2.5	2.5	4A4		1.88	3.73	29.10	
	91513	36.0	38.1	2.1	2.0	4E4		8.05	15.78	119.00	
	91514	41.9	42.7	.8	.8	4E46		7.39	9.26	114.50	
	91515	42.7	44.2	1.5	1.5	4E46		5.75	6.01	119.00	
	91516	44.2	45.7	1.5	1.5	4E46		4.53	7.53	87.80	
	91517	45.7	47.2	1.5	1.5	4G4		4.68	8.60	68.60	
	91518	47.2	48.8	1.6	1.6	4G4		5.30	8.88	81.60	
	91519	48.8	50.3	1.5	1.5	4G0		2.56	5.89	41.50	
	91520	50.3	51.8	1.5	1.5	4G4		3.70	6.65	59.30	
	91521	51.8	53.3	1.5	1.0	4E4		4.95	7.30	68.60	
	91522	54.9	56.4	1.5	.8	4E4		3.15	6.06	51.40	
	91523	56.4	59.1	2.7	1.0	4E46		4.20	8.04	80.60	
	91524	59.1	61.0	1.9	1.9	4E4		6.29	12.70	93.90	
	91525	61.0	62.5	1.5	1.5	4E4\$		4.00	3.60	57.60	
	91526	62.5	64.0	1.5	1.5	4EGD		9.15	15.98	118.60	
	91527	64.0	65.5	1.5	1.5	4E4\$		3.85	4.15	46.30	
	91528	65.5	67.1	1.6	1.5	4EG\$		2.80	1.70	39.80	
	91529	67.1	68.6	1.5	1.4	4E4*		7.58	14.12	127.90	
	91530	68.6	70.2	1.6	1.5	4E4*		3.38	3.80	47.30	
FAGU213	91531	51.2	52.7	1.5	1.1	4E4		3.83	6.86	63.40	
	91532	52.7	54.2	1.5	1.2	4E4#		2.58	4.45	41.50	
	91533	54.2	55.7	1.5	1.4	4E4#		4.23	7.70	58.60	

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK UNIT	CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT
		FROM	TO								
FAGU213	91534	55.7	57.2	1.5	1.1	4G0		3.23	6.12	54.50	
	91535	57.2	58.7	1.5	1.2	4EG4		4.08	7.05	71.70	
	91536	58.7	60.2	1.5	.9	4E4#		5.97	9.17	94.60	
	91537	60.2	61.7	1.5	.9	4EG4		3.85	6.70	50.40	
	91538	61.7	63.2	1.5	.9	4EG4		5.79	8.39	78.90	
	91539	63.2	64.7	1.5	1.1	4E0#		1.50	1.63	31.20	
	91540	64.7	66.2	1.5	.8	4E0#		1.28	1.20	30.20	
	91541	66.2	67.7	1.5	1.0	4E4#		2.75	4.60	52.50	
	91542	67.7	69.2	1.5	1.1	4E0#		1.53	2.45	28.50	
	91543	69.2	70.7	1.5	1.0	4A34		2.93	5.00	46.30	
	91544	70.7	72.2	1.5	1.0	4A30		.85	1.53	17.10	
	91545	72.2	73.7	1.5	.7	4A34		1.83	4.40	24.30	
	91546	73.7	75.2	1.5	.9	4AG		.85	1.83	13.00	
	91547	75.2	76.7	1.5	.9	4AG		.83	1.03	16.10	
	91548	76.7	78.2	1.5	1.0	4AG		1.10	1.88	27.40	
	91549	78.2	79.7	1.5	1.0	4AE		9.14	15.62	120.00	
	91550	79.7	81.2	1.5	1.0	4AE		4.58	8.31	68.60	
	91551	81.2	82.7	1.5	1.3	4AG		.88	1.38	28.10	
	91552	82.7	84.2	1.5	1.3	4A0		.18	.80	12.00	
	91553	84.2	85.7	1.5	1.3	4DE4		6.37	13.89	88.80	
	91554	85.7	87.2	1.5	1.3	4A43		5.70	11.23	70.60	
	91555	87.2	88.7	1.5	1.5	4A43		2.43	4.45	33.30	
	91556	88.7	90.2	1.5	1.5	4A31		.68	1.30	20.20	
	91557	90.2	91.7	1.5	1.4	4A31		.45	1.28	17.10	
	91558	91.7	93.2	1.5	1.3	4A31		.30	1.00	13.00	
	91559	93.2	94.7	1.5	1.3	4A31		.18	.98	12.00	
	91560	94.7	96.2	1.5	1.5	4A31		.20	1.28	6.20	
	91561	96.2	97.7	1.5	1.5	4A31		.88	1.68	12.00	
	91562	97.7	99.2	1.5	1.4	4A31		.43	2.53	11.00	
	91563	99.2	100.7	1.5	1.0	4A31		.05	.85	9.90	
	91564	100.7	102.2	1.5	1.0	4A31		.05	1.03	9.90	
	91565	102.2	103.7	1.5	1.5	4C3		.02	.43	8.90	
	91566	103.7	105.2	1.5	1.5	4E0		.03	1.00	7.90	
	91567	105.2	106.7	1.5	1.5	4AG		.02	.75	5.10	
91568	106.7	108.9	2.2	2.2	4E10		1.28	1.63	29.10		
91569	113.9	114.7	.8	.8	4G4		6.75	12.22	88.80		
FAGU215	90772	4.2	6.0	1.8	.7	4A34		2.95	6.14	53.50	
	90773	7.8	9.3	1.5	1.4	4AL		1.28	2.10	23.30	
	90774	9.3	10.8	1.5	1.5	4AC		1.58	2.33	25.40	
	90775	10.8	12.0	1.2	1.2	4ACL		1.33	2.70	25.40	
	90776	65.5	67.1	1.6	1.0	4G4		5.99	9.17	84.70	
	90777	67.1	68.6	1.5	1.2	4A4		5.10	9.25	86.70	
	90778	68.6	70.1	1.5	1.2	4AL		3.63	6.14	59.30	
	90779	100.6	103.6	3.0	3.0	4A1		.05	.18	2.10	
	90780	103.6	106.7	3.1	2.6	4A1		.05	.38	3.10	
	90781	117.3	118.8	1.5	1.5	4A4		2.23	4.00	38.40	
	90782	118.8	120.4	1.6	1.5	4AG		1.55	2.93	20.20	
90783	129.5	131.1	1.6	.2	4E4		5.96	4.07	71.70		
90784	131.1	132.6	1.5	.2	4L0		2.43	2.60	32.20		
FAGU216	90785	.0	1.5	1.5	.4	4A34		3.88	5.57	65.50	
	90786	1.5	3.0	1.5	1.5	4A34		1.90	4.30	37.40	
	90787	3.0	4.6	1.6	1.6	4A34		2.93	6.17	56.60	
	90788	4.6	6.1	1.5	1.5	4A34		3.95	7.21	70.60	

DDH	SAMPLE	---DEPTHS---		INT	REC	ROCK UNIT	CU %	PB %	ZN %	AG(AA) G/MT	AG(FA) G/MT
		FROM	TO								
FAGU216.	90789	6.1	7.6	1.5	1.5	4A34		5.00	10.06	80.60	
	90790	7.6	9.1	1.5	1.5	4A34		2.58	5.46	41.50	
	90791	9.1	10.7	1.6	1.6	4A34		2.75	6.70	45.30	
	90792	10.7	12.5	1.8	1.7	4A34		1.48	4.38	26.40	
	90793	35.1	36.6	1.5	1.5	4E4		9.57	19.93	138.20	
	90794	36.6	38.1	1.5	1.5	4E4		13.40	21.48	215.70	
	90795	38.1	39.6	1.5	1.5	4E4		10.43	18.62	191.70	
	90796	46.1	48.1	2.0	2.0	4D4		5.55	9.52	96.70	
	90797	49.8	51.8	2.0	2.0	4D0		3.78	3.75	50.40	
	90798	51.8	53.3	1.5	1.5	4A3		1.05	1.35	17.10	
	90969	62.8	64.0	1.2	1.2	3G0		1.68	2.80	30.20	
	90970	64.0	65.5	1.5	1.5	4E4S		5.00	6.30	77.80	
	90971	65.5	67.1	1.6	1.6	4EA		4.15	6.93	61.40	
	90972	67.1	68.6	1.5	1.4	4A1		2.23	2.05	28.50	
	90973	68.6	70.1	1.5	1.4	4A1		1.55	1.83	20.20	
	90974	70.1	71.6	1.5	1.3	4AE4		5.60	10.17	70.60	
	90975	71.6	73.6	2.0	2.0	4EAL		3.50	6.25	52.50	
	90976	94.0	96.0	2.0	1.9	4A0		.23	.35	5.10	
	90977	96.0	97.5	1.5	1.5	4AG		.45	1.20	7.20	
	90978	97.5	99.1	1.6	1.4	4AG		.08	.30	2.10	
	90980	100.6	102.1	1.5	1.4	4A0		.18	.30	3.10	
	90981	103.6	105.2	1.6	1.4	4A0		.08	.10	2.10	
	90982	105.2	106.7	1.5	1.4	4A0		.08	.43	2.10	
	90983	106.7	108.2	1.5	.5	4AE		3.88	7.34	45.30	
	90984	108.2	109.7	1.5	1.0	4AG		.30	.88	5.10	
	90985	123.3	123.8	.5	.5	4D34		9.40	9.30	90.90	
	90986	126.5	128.0	1.5	1.5	4C8		1.88	1.93	18.20	
	90987	128.0	129.5	1.5	1.5	4D8		2.75	2.35	30.20	

TOTAL NUMBER OF ASSAYS 1758