

017921

**KAMLOOPS
RESEARCH & ASSAY
LABORATORY LTD.**

B.C. CERTIFIED ASSAYERS

912 - 1 LAVAL CRESCENT — KAMLOOPS, B.C.
V2C 5P5
PHONE: (604) 372-2784 — TELEX: 048-8320

December 6, 1984

Cyprus Anvil Mining Corporation Ltd.
330 - 355 Burrard Street
Vancouver, B.C.
V6C 2G8

ATTENTION: MR. GREG JILSON

Dear Greg:

Enclosed, please find the revised assays for pyrite and pyrrhotite. The reason that the irons were high was that the original certificate reported the total iron as pyrite and the pyrite iron as pyrrhotite. You will note that we have changed the headings to the correct ones and have added a column for pyrrhotite. I would like to apologize for not spotting this error prior to mailing the certificates. I hope this meets with your approval.

Yours very truly,

Kamloops Research and
Assay Laboratory Ltd.



Derek A. Blundell
President

DAB/rl

cc: Robin Tolbert

Enclosure



KAMLOOPS RESEARCH & ASSAY LABORATORY LTD.

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS
METALLURGISTS

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS B.C.
VIS 1A7

PHONE: (604) 372-2784 — TELEX: 048-8320

CERTIFICATE OF ASSAY

TO Cyprus Anvil Mining Corporation Ltd.

330 - 355 Burrard Street

Vancouver, B.C. V6C 2G8

Certificate No. K-4206

Date August 31, 1981

REVISED

December 6, 1984

I hereby certify that the following are the results of assays made by us upon the herein described Vangorda samples

Sample No.	Marked	Au	Ag	Cu	Fe	Py	As	S.G.	BaO	Po
		grams per tonne	grams per tonne	percent	percent	percent	percent		percent	percent
1	2101	.48	51	.22	29.4	17.7	.04	3.97	1.2	11.7
2	2102	.41	34	.19	25.0	16.4	.13	3.73	1.7	8.6
3	2103	.48	12	.20	23.3	14.8	.06	3.42	.2	8.5
4	2112	.07	8	.03	8.7	4.3	.02	2.94	.9	4.4
5	2113	.14	31	.04	9.5	6.2	.03	3.42	13.2	3.3
6	2114	.41	60	.08	12.6	11.3	.03	4.07	19.6	1.3
7	2115	.48	58	.13	16.9	15.8	.05	4.38	18.9	1.1
8	2116	.82	40	.24	27.4	26.7	.07	4.35	12.7	.7
9	2117	.48	25	.21	25.0	23.0	.06	3.72	1.7	2.0
10	2118	.62	25	.18	25.7	23.4	.06	3.72	2.0	2.3
11	2119	.55	24	.20	29.0	26.7	.05	3.83	2.3	2.3
12	2120	.21	31	.25	17.0	11.0	.05	3.25	7.1	6.0
13	2121	.14	14	.09	13.2	9.7	.03	3.01	1.3	3.5
14	2125	.48	34	.15	25.8	18.5	.07	3.58	2.5	7.3
15	2126	.07	10	.04	8.2	4.5	L.01	2.92	.4	3.7
16	2127	.34	28	.15	21.6	15.1	.05	3.47	3.0	6.5
17	2138	.27	32	.15	23.7	17.9	.05	3.65	6.8	5.8
18	2139	.34	43	.08	15.2	13.5	L.01	3.95	20.4	1.7
19	2140	.27	58	.07	18.1	16.4	L.01	4.15	15.5	1.7
20	2141	.62	50	.06	16.4	12.0	.04	3.73	17.0	4.4

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.

Registered Assayer, Province of British Columbia



Member
Canadian Testing
Association

KAMLOOPS RESEARCH & ASSAY LABORATORY LTD.

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS B.C.

V1S 1A7

PHONE: (604) 372-2784 — TELEX: 048-8320

CERTIFICATE OF ASSAY

B.C. LICENSED ASSAYER
GEOCHEMICAL ANALYSIS
METALLURGISTS

TO Cyprus Anvil Mining Corporation Ltd.

REVISED

Certificate No. K-4206 2

Date August 31, 1981

December 6, 1984

I hereby certify that the following are the results of assays made by us upon the herein described _____ samples

Sl No.	Marked	Au	Ag	Cu	Fe	Py	As	S.G.	BaO	Po
		grams per tonne	grams per tonne	percent	percent	percent	percent		percent	percent
21	2142	.68	42	.10	16.9	12.7	.07	3.62	12.5	4.2
22	2143	1.17	40	.18	23.1	21.0	.14	3.98	12.9	2.1
23	2144	.75	30	.23	27.1	21.6	.23	3.88	9.6	5.5
24	2145	1.17	29	.19	25.7	18.0	.25	3.70	4.4	7.7
25	2146	.21	16	.09	14.2	8.5	.06	3.14	2.5	5.7
26	2147	.34	34	.13	15.6	11.6	.07	3.42	7.1	4.0
27	2148	.34	19	.14	17.8	13.2	.10	3.35	6.2	4.6
28	2153	.14	22	.07	14.1	10.0	.04	3.26	6.9	4.1
29	2158	.96	33	.13	15.1	12.2	.17	3.16	.5	2.9
30	2159	.55	20	.14	16.2	12.1	.12	3.13	.5	4.1
31	2160	.29	8	.09	10.0	6.2	.12	2.93	.2	3.8
32	2161	.48	25	.11	11.8	7.3	.19	3.01	.2	4.5
33	2163	.21	22	.03	7.4	5.9	.14	2.92	.5	1.5
34	2164	.27	22	.05	11.2	7.0	.17	3.57	.6	4.2
35	2165	.21	16	.04	11.5	7.4	.06	2.99	1.2	4.1
36	2166	.21	24	.06	14.1	10.6	.07	3.28	.9	3.5
37	2167	.07	9	.02	7.4	3.5	.07	2.92	.7	3.9
38	2168	L.01	5	.02	5.9	1.5	.06	2.89	1.1	4.4
39	2169	L.01	5	.01	5.6	1.2	.04	2.84	.6	4.4
40	2170	.55	43	.12	19.9	14.1	.08	3.65	4.7	5.8

NOTE:

Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.

Registered Assayer, Province of British Columbia



KAMLOOPS RESEARCH & ASSAY LABORATORY LTD.

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS
METALLURGISTS

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS B.C.
VIS 1A7

PHONE: (604) 372-2784 — TELEX: 048-8320

CERTIFICATE OF ASSAY

TO Cyprus Anvil Mining Corporation Ltd.

Certificate No. K-4206 3

REVISED

Date August 31, 1981

December 6, 1984

I hereby certify that the following are the results of assays made by us upon the herein described _____ samples

Anal No.	Marked	Au	Ag	Cu	Fe	Py	As	S.G.	BaO	Po
		grams per tonne	grams per tonne	percent	percent	percent	percent		percent	percent
41	2171	.17	29	.17	26.1	19.4	.07	3.92	6.9	6.7
42	2172	.34	48	.09	13.2	9.9	.14	3.31	.6	3.3
43	2173	.27	33	.07	10.6	7.7	.10	3.17	.3	2.9
44	2183	.48	34	.12	13.7	7.3	.12	3.19	1.7	6.4
45	2184	.82	52	.34	34.0	27.8	.29	4.26	.9	6.2
46	2185	.89	55	.34	35.6	30.4	.36	4.50	.6	5.2
47	2186	.75	82	.15	31.6	21.2	.14	4.44	7.8	10.4
48	2188	.62	73	.15	33.8	19.8	.13	4.39	6.1	14.0
49	2189	1.10	53	.23	32.9	25.4	.09	4.59	9.2	7.5
50	2190	.75	33	.25	33.3	25.3	.07	4.29	6.3	8.0
51	2192	.41	22	.13	21.8	14.6	.05	3.57	4.0	7.2
52	2193	.48	19	.09	14.9	9.7	.05	3.14	1.4	5.2
53	2194	.21	19	.10	20.4	13.9	.06	3.36	1.1	6.5
54	2195	.27	26	.13	16.6	11.7	.13	3.27	1.1	4.9
55	2196	.27	20	.07	7.7	4.6	.14	2.96	.3	3.1
56	2197	.14	20	.27	9.0	4.7	.10	3.07	5.0	4.3
57	2198	.21	26	.24	6.4	5.5	.07	3.07	2.9	.9
58	2199	.68	32	.25	17.7	15.6	.16	3.52	5.2	2.1
59	2200	.82	40	.19	31.2	23.1	.16	4.20	3.2	8.1
60	2206	.34	17	.11	18.9	13.9	.20	3.38	3.3	5.0

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.



Registered Assayer, Province of British Columbia



KAMLOOPS RESEARCH & ASSAY LABORATORY LTD.

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS
METALLURGISTS

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS B.C.
VIS 1A7

PHONE: (604) 372-2784 — TELEX: 048-8320

CERTIFICATE OF ASSAY

TO Cyprus Anvil Mining Corporation Ltd.

Certificate No. K-4206 4

REVISED

Date August 31, 1981

December 6, 1984

I hereby certify that the following are the results of assays made by us upon the herein described _____ samples

Kral No.	Marked	Au	Ag	Cu	Fe	Py	As	S.G.	BaO	Po
		grams per tonne	grams per tonne	percent	percent	percent	percent		percent	percent
61	2207	.48	31	.08	14.4	11.7	.27	3.26	3.3	2.7
62	2208	.34	30	.09	14.3	10.3	.22	3.25	1.7	4.0
63	2209	.07	12	.06	7.9	3.7	.12	2.94	.4	4.2
64	2210	L.01	4	.03	5.5	1.6	.05	2.88	.3	3.9
65	2211	.34	23	.11	18.4	12.2	.12	3.40	2.3	6.2
66	2212	.48	27	.27	27.6	22.8	.13	3.80	1.8	4.8
67	2213	.82	31	.44	22.2	19.5	.10	3.70	2.9	2.7
68	2214	.41	76	.65	19.3	11.4	.09	4.13	13.7	7.9
69	2215	.62	41	.31	25.5	11.5	.19	3.65	2.2	14.0
70	2216	.34	20	.22	24.7	11.7	.12	3.48	.6	13.0
71	2217	.32	13	.38	21.5	12.1	.09	3.38	.8	9.4
72	2218	.21	9	.24	17.2	10.4	.09	3.23	.6	6.8
73	2219	.21	10	.23	16.9	10.8	.07	3.30	.5	6.1
74	2225	.27	23	.26	20.1	19.3	.04	3.47	2.4	.8
75	2226	.21	36	.38	22.6	16.6	.09	3.70	5.4	6.0
76	2227	.21	27	.26	25.0	11.3	.05	3.80	4.7	13.7
77	2228	.34	31	.31	25.6	23.0	.11	3.73	2.0	2.6
78	2229	.27	50	.32	14.6	12.1	.05	4.20	18.1	2.5
79	2230	.27	56	.19	12.7	11.9	.03	4.20	19.3	.8
80	2231	.27	61	.06	13.3	11.4	.02	4.35	21.8	1.9

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.

Registered Assayer, Province of British Columbia



Member
Canadian Testing
Association

KAMLOOPS RESEARCH & ASSAY LABORATORY LTD.

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS B.C.

V1S 1A7

PHONE: (604) 372-2784 — TELEX: 048-8320

CERTIFICATE OF ASSAY

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS
METALLURGISTS

TO Cyprus Anvil Mining Corporation Ltd.

REVISED

December 6, 1984

Certificate No. K-4206 5

Date August 31, 1981

I hereby certify that the following are the results of assays made by us upon the herein described _____ samples

al No.	Marked	Au grams per tonne	Ag grams per tonne	Cu percent	Fe percent	Py percent	As percent	S.G.	BaO percent	Po percent
81	2232	.27	54	.15	16.3	12.9	.03	4.24	16.8	3.4
82	2233	.82	92	.10	22.9	9.2	.18	4.18	14.7	13.7
83	2234	.89	83	.13	28.9	11.4	.08	4.00	5.2	17.5
84	2235	.41	34	.21	29.6	21.0	.09	4.02	4.1	8.6
85	2236	.27	22	.26	28.6	22.5	.11	3.86	3.1	6.1
86	2237	.41	20	.33	28.0	23.5	.13	3.77	2.2	4.5
87	2238	1.10	16	.42	26.6	21.8	.30	3.73	2.9	4.8
88	2239	.34	16	.29	21.2	15.8	.06	3.52	5.2	5.4
89	2240	.21	10	.40	17.7	11.6	.06	3.37	3.7	6.1
90	2241	.41	38	1.07	27.8	18.9	.07	3.64	1.3	8.9
91	2242	.41	36	.35	30.6	18.2	.03	3.75	2.1	12.4
92	2243	.27	29	.37	25.8	15.3	.03	3.68	3.9	10.5
93	2246	.48	49	.15	15.7	12.0	.11	3.47	7.7	3.7
94	2247	.07	6	.14	8.5	4.6	.08	2.85	.4	3.9
95	2266	.14	15	.05	5.4	3.8	1.46	3.02	2.8	1.6
96	2267	.62	50	.09	8.4	7.7	1.53	3.32	15.0	.7
97	2268	.55	65	.09	11.8	10.9	1.40	3.75	18.7	.9
98	2269	.48	57	.08	13.8	11.8	.82	4.17	16.2	2.0
99	2270	.21	21	.05	6.5	4.5	1.21	3.13	6.2	2.0
100	2271	.14	12	.05	5.4	3.5	1.26	2.96	3.6	1.9

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.

Registered Assayer, Province of British Columbia



KAMLOOPS RESEARCH & ASSAY LABORATORY LTD.

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS B.C.
V1S 1A7

PHONE: (604) 372-2784 — TELEX: 048-8320

CERTIFICATE OF ASSAY

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS
METALLURGISTS

TO Cyprus Anvil Mining Corporation Ltd.

REVISED

Certificate No. K-4206 6

December 6, 1984

Date August 31, 1981

I hereby certify that the following are the results of assays made by us upon the herein described Vangorda samples

Kral No.	Marked	Au	Ag	Cu	Fe	Py	As	S.G.	BaO	Po
		grams per tonne	grams per tonne	percent	percent	percent	percent		percent	percent
101	2272	.14	16	.03	6.3	3.2	1.23	3.00	3.7	3.1
102	2273	.14	16	.04	7.1	3.9	1.08	3.04	3.1	3.2
103	2298	.55	19	.15	25.7	17.7	.07	3.55	.8	8.0
104	2299	.21	26	.16	20.8	15.1	.14	3.38	.3	5.7
105	2301	.62	22	.22	33.4	26.7	.18	4.00	.3	6.7
106	2302	.34	22	.25	23.0	20.3	.12	3.82	.2	2.7
107	2303	.34	14	.24	21.4	18.7	.09	3.71	.3	2.7
108	2304	.75	48	.21	36.9	21.7	.10	3.95	.2	15.2
109	2305	1.58	60	.25	34.6	19.6	.11	4.29	.4	15.0
110	2306	1.17	51	.25	34.3	22.2	.09	4.33	6.7	12.1
111	2307	.55	27	.28	41.1	29.8	.10	4.31	.5	11.3
112	2308	.82	31	.29	27.9	15.9	.18	3.68	.4	12.0
113	2309	1.37	35	.28	18.1	10.6	.51	3.52	.4	7.5
114	2320	.14	31	.04	9.0	4.7	.06	3.41	11.6	4.3
115	2321	.89	54	.14	16.2	12.5	.09	3.91	17.5	3.7
116	2322	.82	39	.30	22.6	17.7	.10	3.77	9.4	4.9
117	2328	.82	70	.15	11.9	10.0	.19	3.53	16.2	1.9
118	2329	1.03	72	.24	21.0	19.1	.16	3.95	15.3	1.9
119	2330	.96	51	.20	18.3	15.1	.17	3.64	9.3	3.2
120	2331	.48	34	.13	16.5	13.0	.16	3.42	7.5	3.5

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.





KAMLOOPS RESEARCH & ASSAY LABORATORY LTD.

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS
METALLURGISTS

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS B.C.
V1S 1A7

PHONE: (604) 372-2784 — TELEX: 048-8320

CERTIFICATE OF ASSAY

TO Cyprus Anvil Mining Corporation Ltd.

REVISED

Certificate No. K-4206 7

December 6, 1984

Date August 31, 1981

I hereby certify that the following are the results of assays made by us upon the herein described _____ samples

Kral No.	Marked	Au grams per tonne	Ag grams per tonne	Cu percent	Fe percent	Py percent	As percent	S.G.	BaO percent	Po percent
121	2332	.41	27	.14	16.8	11.7	.13	3.29	5.9	5.1
122	2333	.68	49	.15	25.3	18.6	.05	4.08	14.3	6.7
123	2334	.75	37	.23	26.2	18.1	.06	3.95	11.7	8.1
124	2335	.27	10	.06	11.8	6.0	.05	3.07	1.1	5.8
125	2343	.96	27	.32	17.8	16.1	.75	3.47	.6	1.7
126	2344	1.51	28	.41	17.2	16.6	.59	3.82	.6	.6
127	2345	.68	84	.41	24.3	24.1	.14	4.63	18.2	.2
128	2346	1.65	113	.34	24.4	24.0	.08	4.72	17.9	.4
129	2347	.96	85	.40	33.6	32.9	.14	4.76	4.9	.7
130	2348	.82	50	.27	35.9	31.2	.08	4.67	5.2	4.7
131	2349	.21	13	.08	17.5	12.9	.04	3.27	1.8	4.6
132	2350	.21	25	.07	10.3	6.3	.07	3.13	2.9	4.0
133	2351	1.23	41	.20	31.8	26.7	.24	4.33	5.4	5.1
134	2352	.55	20	.14	22.3	17.1	.08	3.34	7.2	5.2
135	2356	.82	118	.77	17.9	16.2	.09	4.02	15.1	1.7
136	2357	.89	75	.58	20.2	19.4	.09	3.62	2.5	.8
137	2358	1.10	80	.41	26.6	21.5	.15	4.37	4.9	5.1
138	2359	.82	81	.15	25.2	16.9	.07	4.39	16.2	8.3
139	2360	.41	56	.07	12.1	9.3	.06	3.48	15.2	2.8
140	2361	.21	14	.10	12.2	4.9	.05	3.12	3.0	7.3

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.

R. Brown



KAMLOOPS RESEARCH & ASSAY LABORATORY LTD.

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS
METALLURGISTS

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS B.C.
V1S 1A7

PHONE: (604) 372-2784 — TELEX: 048-8320

CERTIFICATE OF ASSAY

TO Cyprus Anvil Mining Corporation Ltd.

REVISED

Certificate No. K-4206 8

December 6, 1984

Date August 31, 1981

I hereby certify that the following are the results of assays made by us upon the herein described Vangorda samples

Kral No.	Marked	Au	Ag	Cu	Fe	Py.	As	S.G.	BaO	Po
		grams per tonne	grams per tonne	percent	percent	percent	percent		percent	percent
141	2362	.62	44	.22	25.3	18.6	.08	4.10	10.6	6.7
142	2363	.27	17	.09	13.5	8.7	.10	3.22	1.4	4.8
143	2364	.14	19	.15	16.3	9.1	.11	3.26	3.0	7.2
144	2365	.41	31	.20	29.6	21.8	.07	4.02	6.7	7.8
145	2366	.21	15	.08	25.6	22.8	.08	3.77	.9	2.8
146	2367	.14	11	.06	30.5	28.7	.07	3.89	.6	1.8
147	2368	.21	18	.12	21.8	17.9	.07	3.42	.5	3.9
148	2379	.21	42	.06	12.0	8.9	.08	3.46	9.1	3.1
149	2380	.14	36	.04	12.1	8.3	.08	3.29	5.5	3.8
150	2381	.07	10	.02	7.5	3.7	.03	2.97	1.5	3.6
151	2382	.41	30	.09	18.7	15.3	.09	3.58	6.2	3.4
152	2383	.68	43	.15	24.6	20.7	.06	4.39	14.4	3.9
153	2384	.55	43	.16	24.6	19.2	.10	3.68	6.6	5.4
154	2385	L.01	20	.06	8.4	5.6	.08	2.96	.3	2.8
155	2393	.07	28	.12	21.5	14.8	.05	3.68	2.4	6.7
156	2394	.34	45	.13	26.7	20.4	.12	3.97	1.1	6.3
157	2395	.34	19	.10	20.2	15.6	.49	3.48	.6	4.6
158	2396	.55	18	.15	27.6	22.4	.30	3.77	.5	5.2
159	2397	.48	24	.28	35.0	31.8	.29	4.29	.4	3.2
160	3702	L.01	1	.02	5.3	1.7	.05	2.82	.6	3.6

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.

Registered Assayer, Province of British Columbia



KAMLOOPS RESEARCH & ASSAY LABORATORY LTD.

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS
METALLURGISTS

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS B.C.
V1S 1A7

PHONE: (604) 372-2784 — TELEX: 048-8320

CERTIFICATE OF ASSAY

TO Cyprus Anvil Mining Corporation Ltd.

REVISED

Certificate No. K-4206 9

December 6, 1984

Date August 31, 1981

I hereby certify that the following are the results of assays made by us upon the herein described _____ samples

Kral No.	Marked	Au	Ag	Cu	Fe	Py	As	S.G.	BaO	Po
		grams per tonne	grams per tonne	percent	percent	percent	percent		percent	percent
161	3703	.14	16	.04	9.2	6.3	.03	3.12	4.6	2.9
162	3704	.14	52	.05	17.2	14.3	.01	3.52	3.2	2.9
163	3705	.14	65	.04	22.3	12.2	.02	3.62	4.7	10.1
164	3706	.07	34	.03	12.1	6.8	L.01	3.22	7.0	5.3
165	3707	.03	11	.02	7.1	3.0	.05	2.97	1.3	4.1
166	3708	L.01	4	.02	6.3	2.4	.03	2.85	.6	3.9
167	3709	.07	18	.11	10.6	6.4	.04	3.06	1.2	4.2
168	3710	.21	31	.27	25.2	21.0	.05	3.66	1.6	4.2
169	3711	.14	25	.32	21.6	18.5	.06	3.50	2.6	3.1
170	3712	.14	27	.31	20.4	16.9	.07	3.51	2.4	3.5
171	3713	.07	14	.18	14.2	11.0	.04	3.21	1.0	3.2
172	3714	.07	12	.15	12.4	9.1	.02	3.26	.8	3.3
173	3715	.07	10	.11	9.3	6.0	.03	2.98	.8	3.3
174	3716	.21	15	.15	17.8	14.3	.04	3.39	2.5	3.5
175	3717	.34	21	.17	23.9	17.1	.04	3.69	4.0	6.8
176	3718	.21	8	.09	13.7	9.9	.05	3.11	.9	3.8
177	3719	.27	13	.12	16.4	11.4	.01	3.23	.6	5.0
178	3720	.21	22	.13	20.8	14.3	.04	3.52	.7	6.5
179	3721	.14	13	.14	16.0	10.4	.04	3.23	.4	5.6
180	3722	L.01	2	.06	6.9	2.9	.01	2.84	L.1	4.0

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.

Registered Assayer, Province of British Columbia



KAMLOOPS RESEARCH & ASSAY LABORATORY LTD.

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS B.C.
V1S 1A7

PHONE: (604) 372-2784 — TELEX: 048-8320

CERTIFICATE OF ASSAY

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS
METALLURGISTS

TO Cyprus Anvil Mining Corporation Ltd.

Certificate No. K-4206 10

REVISED

Date August 31, 1981

December 6, 1984

I hereby certify that the following are the results of assays made by us upon the herein described Vangorda samples

Kral No.	Marked	Au grams per tonne	Ag grams per tonne	Cu percent	Fe percent	Py percent	As percent	S.G.	BaO percent	Po percent
181	3744	.21	28	.11	15.5	12.4	.09	3.45	4.3	3.1
182	3745	.55	68	.18	25.8	22.8	.19	4.33	8.9	3.0
183	3746	.96	58	.12	20.7	15.4	.14	4.18	10.4	5.3
184	3747	L.01	4	.02	5.6	1.5	.07	2.93	.8	4.1
185	3748	.07	2	.02	5.8	1.8	.14	2.92	1.2	4.0
186	3749	.07	5	.03	6.4	1.8	.03	2.85	1.0	4.6
187	3750	.14	22	.18	21.7	17.9	.05	3.53	1.2	3.8
188	3751	.14	19	.12	19.7	13.7	.05	3.36	.4	6.0
189	3752	.41	11	.27	16.2	7.2	.01	3.16	.2	9.0
190	3753	.14	7	.21	16.7	8.1	.03	3.14	.1	8.6
191	3754	.14	17	.11	12.0	6.0	.02	3.21	4.1	6.0
192	3755	1.10	47	.14	25.9	18.4	.10	4.20	8.1	7.5
193	3756	.96	35	.21	34.4	25.6	.13	4.37	.2	8.8
194	3757	.55	27	.19	30.5	24.4	.21	4.15	1.2	6.1
195	3758	.55	16	.09	14.6	10.4	.13	3.26	3.1	4.2
196	3769	.34	26	.05	7.5	.1	.11	2.92	5.1	7.4
197	3770	1.10	119	.08	12.7	.5	.17	3.08	4.4	12.2
198	3771	1.10	229	.17	13.0	8.8	.17	3.36	8.9	4.2
199	3772	.48	85	.23	9.1	5.8	.10	3.01	5.9	3.3
200	3773	.14	20	.10	5.3	2.0	.05	2.85	1.4	3.3

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.

Registered Assayer, Province of British Columbia



KAMLOOPS RESEARCH & ASSAY LABORATORY LTD.

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS
METALLURGISTS

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS B.C.
V1S 1A7

PHONE: (604) 372-2784 — TELEX: 048-8320

CERTIFICATE OF ASSAY

TO Cyprus Anvil Mining Corporation Ltd.

Certificate No. K-4206 11

REVISED

Date August 31, 1981

December 6, 1984

I hereby certify that the following are the results of assays made by us upon the herein described Vangorda samples

Kral No.	Marked	Au	Ag	Cu	Fe	Py	As	S.G.	BaO	Po
		grams per tonne	grams per tonne	percent	percent	percent	percent		percent	percent
201	3774	.07	8	.05	5.0	1.6	.04	2.87	.8	3.4
202	3775	L.01	8	.05	5.7	2.5	.09	2.87	1.4	3.2
203	3776	.27	47	.15	13.3	9.2	.06	3.32	7.1	4.1
204	3777	.34	63	.15	19.0	15.1	.11	4.02	13.6	3.9
205	3778	.41	75	.18	22.4	16.0	.10	4.33	14.7	6.4
206	3779	.48	76	.14	18.9	14.6	.06	4.31	19.1	4.3
207	3780	.82	55	.17	26.6	23.7	.07	4.88	15.1	2.9
208	3781	.68	58	.12	25.2	22.2	.07	4.44	15.7	3.0
209	3782	.75	31	.14	30.6	25.5	.08	3.97	5.8	5.1
210	3783	.55	23	.20	31.8	27.4	.16	4.07	2.0	4.4
211	3784	.75	33	.20	33.0	27.5	.12	4.10	3.9	5.5
212	3785	.62	47	.14	28.3	21.6	.05	4.41	14.6	6.7
213	3786	.68	28	.17	33.1	27.6	.11	4.29	7.1	5.5
214	3787	.40	20	.19	28.5	25.3	.14	3.83	3.4	3.2
215	3788	.62	32	.26	27.0	22.9	.10	3.83	5.2	4.1
216	3789	.34	27	.25	25.8	23.9	.19	3.77	2.7	1.9
217	3790	.41	22	.29	31.7	28.8	.22	4.02	1.3	2.9
218	3796	.68	81	.78	24.8	18.5	.11	3.30	9.2	6.3
219	3797	.55	66	.16	22.8	11.8	.04	3.83	4.7	11.0
220	3798	.62	57	.17	20.9	11.3	.07	3.42	2.2	9.6

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.

Registered Assayer, Province of British Columbia



KAMLOOPS RESEARCH & ASSAY LABORATORY LTD.

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS
METALLURGISTS

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS B.C.
VIS 1A7

PHONE: (604) 372-2784 — TELEX: 048-8320

CERTIFICATE OF ASSAY

TO Cyprus Anvil Mining Corporation Ltd.

REVISED

Certificate No. K-4206 12

December 6, 1984

Date August 31, 1981

I hereby certify that the following are the results of assays made by us upon the herein described Vangorda samples

Kral No.	Marked	Au	Ag	Cu	Fe	Py	As	S.G.	8a0	Po
		grams per tonne	grams per tonne	percent	percent	percent	percent		percent	percent
221	3799	1.37	84	.21	25.1	20.1	.06	4.12	9.5	5.0
222	3800	1.10	71	.22	29.1	21.2	.07	4.17	6.8	7.9
223	3801	1.03	71	.19	28.6	22.7	.07	4.37	10.4	5.9
224	3802	1.10	72	.19	28.3	22.6	.06	4.12	12.9	5.7
225	3803	1.10	63	.18	26.4	19.1	.08	4.12	8.6	7.8
226	3804	1.37	77	.19	28.9	24.3	.09	4.39	7.3	4.6
227	3805	1.23	78	.18	28.8	23.9	.09	4.41	7.2	4.9
228	3806	1.10	78	.19	27.2	20.5	.08	4.07	5.2	6.7
229	3807	1.78	62	.20	26.8	17.7	.06	4.05	5.2	9.1
230	3808	1.51	63	.24	28.8	21.9	.04	4.08	4.8	6.9
231	3809	1.23	56	.25	30.9	25.9	.05	4.25	4.4	5.0
232	3810	1.71	64	.26	30.6	26.9	.06	4.17	5.2	3.7
233	3811	1.44	65	.26	30.0	26.4	.06	4.15	5.6	3.6
234	3812	1.44	61	.24	30.2	27.1	.05	4.44	6.5	3.1
235	3813	1.71	67	.23	34.3	31.9	.07	4.42	7.9	2.4
236	3814	1.44	62	.22	26.2	23.2	.02	4.20	6.6	3.0
237	3815	1.37	71	.22	28.2	26.0	.03	4.39	6.6	2.2
238	3816	1.37	71	.21	26.8	24.0	.06	4.31	6.2	2.8
239	3817	1.10	72	.21	27.5	25.1	.05	4.35	5.9	2.4
240	3818	1.17	70	.20	26.0	23.7	.06	4.18	5.7	2.3

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.

Registered Assayer, Province of British Columbia



KAMLOOPS RESEARCH & ASSAY LABORATORY LTD.

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS B.C.

V1S 1A7

PHONE: (604) 372-2784 — TELEX: 048-8320

CERTIFICATE OF ASSAY

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS
METALLURGISTS

TO Cyprus Anvil Mining Corporation Ltd.

REVISED

Certificate No. K-4206 13

December 6, 1984

Date August 31, 1981

I hereby certify that the following are the results of assays made by us upon the herein described Vangorda samples

Kral No.	Marked	Au grams per tonne	Ag grams per tonne	Cu percent	Fe percent	Py percent	As percent	S.G.	BaO percent	Po percent
241	3819	1.23	65	.19	26.0	23.5	.04	4.15	6.5	2.5
242	3820	1.30	64	.19	27.1	24.5	.05	4.39	5.8	2.6
243	3821	.21	48	.07	18.2	16.9	.07	4.44	26.4	1.3
244	3822	.27	41	.10	25.1	19.2	.06	4.37	19.0	5.9
245	3823	.48	27	.23	30.5	15.0	.16	3.71	4.7	15.5
246	3824	1.44	21	.19	32.6	24.5	.30	4.16	4.4	8.1
247	3825	.24	62	.19	31.6	9.9	.17	4.00	.9	21.7
248	3826	.41	46	.16	33.6	17.5	.14	4.22	3.5	16.1
249	3827	.41	35	.19	28.2	27.1	.10	3.77	2.3	1.1
250	3828	.27	9	.22	25.6	12.2	L.01	3.29	.3	13.4
251	3829	.41	1	.24	21.3	9.9	.05	3.13	.1	11.4
252	3830	.34	6	.20	19.0	8.0	.12	3.38	.3	11.0
253	3831	.41	15	.45	21.3	8.1	.06	3.24	.1	13.2
254	3832	.21	8	.20	16.0	7.3	.02	3.25	L.1	8.7
255	3833	.21	3	.21	17.9	8.6	.06	3.28	L.1	9.3
256	3849	.21	14	.23	23.0	16.9	.07	3.58	2.7	6.1
257	3850	.48	21	.33	31.0	24.0	.04	4.07	6.1	7.0
258	3851	.21	18	.25	25.1	18.9	.04	3.52	2.0	6.2
259	3852	.21	15	.21	18.1	14.1	.07	3.28	4.4	4.0
260	3853	.14	8	.09	19.1	16.8	.11	3.10	2.6	2.3

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.



Registered Assayer, Province of British Columbia



KAMLOOPS RESEARCH & ASSAY LABORATORY LTD.

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS
METALLURGISTS

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS B.C.
V1S 1A7

PHONE: (604) 372-2784 — TELEX: 048-8320

CERTIFICATE OF ASSAY

TO Cyprus Anvil Mining Corporation Ltd.

REVISED

Certificate No. K-4206 14

December 6, 1984

Date August 31, 1981

I hereby certify that the following are the results of assays made by us upon the herein described Vangorda samples

Kral No.	Marked	Au	Ag	Cu	Fe	Py	As	S.G.	BaO	Po
		grams per tonne	grams per tonne	percent	percent	percent	percent		percent	percent
261	3854	.21	19	.21	25.5	21.5	.08	3.72	2.0	4.0
262	3855	.07	7	.09	10.1	3.3	.07	3.06	2.2	6.8
263	3868	.27	22	.06	5.4	2.5	.09	2.89	3.1	2.9
264	3869	.34	38	.08	10.2	6.7	.10	3.25	13.8	3.5
265	3870	.82	72	.17	21.5	17.8	.12	4.02	12.5	3.7
266	3871	.82	67	.17	14.8	12.2	.11	3.66	14.6	2.6
267	3872	.69	44	.15	12.9	9.9	.11	3.44	11.0	3.0
268	3873	.75	43	.24	17.3	14.5	.09	3.69	13.9	2.8
269	3874	.96	34	.17	27.0	23.8	.10	4.12	8.7	3.2
270	3875	.82	24	.31	31.1	28.5	.17	3.75	1.8	2.6
271	3876	1.09	26	.30	37.9	33.5	.27	3.82	.1	4.4
272	3877	1.23	28	.18	37.4	25.1	.16	4.22	.7	12.3
273	3878	.96	84	.10	20.4	16.2	.08	4.48	22.0	4.2
274	3879	1.65	104	.10	13.8	12.0	.09	4.59	27.0	1.8
275	3880	1.17	55	.12	26.0	18.9	.24	3.97	7.9	7.1
276	3881	1.17	40	.16	23.1	17.8	.30	3.52	3.9	5.3
277	3882	1.03	29	.29	23.1	20.4	.39	3.16	1.0	2.7
278	3883	1.37	36	.22	23.5	20.0	.29	3.70	5.2	3.5
279	3884	.96	26	.19	24.8	14.5	.49	3.58	.3	10.3
280	3896	.89	27	.25	30.6	22.0	.25	3.72	1.6	8.6

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.

Registered Assayer, Province of British Columbia



KAMLOOPS RESEARCH & ASSAY LABORATORY LTD.

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS
METALLURGISTS

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS B.C.
VIS 1A7

PHONE: (604) 372-2784 — TELEX: 048-8320

CERTIFICATE OF ASSAY

TO Cyprus Anvil Mining Corporation Ltd.

REVISED

Certificate No. K-4206 15

December 6, 1984

Date August 31, 1981

I hereby certify that the following are the results of assays made by us upon the herein described Vangorda samples

Kral No.	Marked	Au grams per tonne	Ag grams per tonne	Cu percent	Fe percent	Py percent	As percent	S.G.	BaO percent	Po percent
281	3897	.89	25	.39	30.2	14.1	.10	3.62	.7	16.1
282	3898	.89	21	.44	30.6	15.3	.08	3.96	.4	15.3
283	3899	.96	14	.31	28.8	17.9	.16	3.68	.3	10.9
284	3900	.89	17	.27	26.5	22.1	.24	3.72	.4	4.4
285	3907	.41	30	.16	26.8	13.9	.06	3.76	.2	12.9
286	3908	.34	25	.14	22.0	13.4	.07	3.57	.2	8.6
287	3910	.21	30	.05	11.1	7.0	.17	3.13	.2	4.1
288	3916	.07	10	.03	4.7	1.0	.06	2.82	5.7	3.7
289	3917	.07	49	.04	10.0	5.1	.07	3.72	23.2	4.9
290	3918	.14	60	.08	17.0	6.5	.06	3.56	9.9	10.5
291	3919	.48	80	.04	14.5	9.0	.04	4.15	22.7	5.5
292	3920	.34	71	.04	14.4	8.5	.03	4.23	27.6	5.9
293	3921	.34	87	.11	21.7	5.6	.05	3.97	16.2	16.1
294	3922	.41	82	.15	23.9	4.4	.08	3.75	7.9	19.5
295	3923	.89	44	.13	21.1	5.9	.04	3.46	8.6	15.2
296	3924	.55	24	.17	23.9	12.9	.05	3.47	5.9	11.0
297	3925	.67	15	.25	25.2	13.2	.03	3.42	1.6	12.0
298	3926	2.33	22	.22	24.1	10.1	.04	3.55	1.7	14.0
299	3927	.69	12	.22	23.9	7.2	.09	3.29	.9	16.7
300	3944	.62	44	.18	23.2	15.7	.20	3.92	14.4	7.5

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.

Registered Assayer, Province of British Columbia



KAMLOOPS RESEARCH & ASSAY LABORATORY LTD.

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS
METALLURGISTS

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS B.C.

VIS 1A7

PHONE: (604) 372-2784 — TELEX: 048-8320

CERTIFICATE OF ASSAY

TO Cyprus Anvil Mining Corporation Ltd.

Certificate No. K-4206 16

REVISED

Date August 31, 1981

December 6, 1984

I hereby certify that the following are the results of assays made by us upon the herein described Vangorda samples

Kral No.	Marked	Au	Ag	Cu	Fe	Py	As	S.G.	BaO	Po
		grams per tonne	grams per tonne	percent	percent	percent	percent		percent	percent
301	3945	1.58	30	.24	26.5	20.8	.52	3.59	.8	5.7
302	3946	1.17	22	.29	27.0	24.8	.41	3.70	.5	2.2
303	3947	.69	16	.30	26.5	22.7	.20	3.53	.6	3.8
304	3948	1.10	21	.25	28.6	21.7	.26	3.62	.9	6.9
305	3949	.82	29	.25	26.8	19.7	.29	3.70	6.4	7.1
306	3950	1.51	33	.26	31.4	15.9	.07	3.72	1.4	15.5
307	3951	1.85	31	.22	27.6	13.0	.08	3.70	1.6	14.6
308	3952	.82	42	.16	29.5	7.4	.04	3.77	1.1	22.1
309	3953	.48	23	.18	31.8	12.1	.02	3.79	1.2	19.7
310	3954	.41	23	.20	31.7	17.1	.04	3.83	1.3	14.6
311	3955	.62	34	.15	24.6	14.1	.03	3.77	9.4	10.5
312	3956	.75	74	.14	23.5	11.0	.15	3.91	10.8	12.5
313	3957	.75	35	.21	25.6	11.8	.18	3.94	6.4	13.8
314	3958	.62	16	.23	25.3	8.2	.03	3.43	1.0	17.1
315	3959	1.30	12	.20	23.2	7.9	.03	3.14	.6	15.3
316	3960	.82	18	.32	25.3	8.6	.02	3.44	.5	16.7
317	3965	.82	68	.16	26.6	21.1	.16	4.31	10.7	5.5
318	3966	.41	41	.11	18.1	12.5	.23	3.60	6.9	6.6
319	3967	.75	87	.11	16.2	12.8	.13	4.33	21.9	3.4
320	3968	1.30	94	.11	14.8	12.9	.16	4.48	20.3	1.9

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.

Registered Assayer, Province of British Columbia



KAMLOOPS RESEARCH & ASSAY LABORATORY LTD.

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS
METALLURGISTS

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS B.C.

VIS 1A7

PHONE: (604) 372-2784 — TELEX: 048-8320

CERTIFICATE OF ASSAY

TO Cyprus Anvil Mining Corporation Ltd.

REVISED

Certificate No. K-4206 17

December 6, 1984

Date August 31, 1981

I hereby certify that the following are the results of assays made by us upon the herein described Vangorda samples

Kral No.	Marked	Au grams per tonne	Ag grams per tonne	Cu percent	Fe percent	Py percent	As percent	S.G.	BaO percent	Po percent
321	3969	2.47	198	.22	19.1	17.6	.21	4.50	2.0	1.5
322	3970	1.78	128	.17	18.0	15.8	.14	4.50	23.8	2.2
323	3971	1.23	92	.13	17.4	14.9	.08	4.59	27.6	2.5
324	3972	1.44	86	.12	25.1	18.8	.07	4.59	11.0	6.3
325	3973	1.44	87	.12	26.3	18.8	.08	4.61	11.2	7.5
326	3974	1.71	84	.15	28.0	23.1	.21	4.48	8.8	4.9
327	3975	.62	33	.12	16.3	11.6	.06	3.34	2.4	4.7
328	3976	.48	19	.12	12.0	6.0	.03	3.07	.6	6.0
329	3977	.41	15	.09	10.4	3.8	.03	2.99	.3	6.6
330	3978	.55	74	.15	18.1	14.4	.14	3.58	2.4	3.7
331	3979	.07	10	.14	9.3	2.6	.04	2.90	L.1	6.7
332	3980	.07	7	.22	9.6	4.6	.04	2.93	L.1	5.0
333	3981	.07	4	.08	9.1	3.3	.02	2.96	.2	5.8
334	4000	.96	63	.20	23.9	16.8	.09	4.13	13.0	7.1
335	6004	.07	8	.08	11.8	2.8	.01	3.04	.4	9.0
336	6005	.07	23	.15	10.9	4.9	.03	3.41	14.3	6.0
337	6006	.27	38	.12	16.2	13.0	.10	3.66	13.8	3.2
338	6007	.14	16	.14	16.9	12.4	.06	3.19	1.0	4.5
339	6008	L.01	27	.03	10.2	5.6	.02	3.24	5.8	4.6
340	6009	.27	64	.05	12.0	9.9	.01	3.82	19.2	2.1

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.

Registered Assayer, Province of British Columbia



KAMLOOPS RESEARCH & ASSAY LABORATORY LTD.

B.C. LICENSED ASSAYERS
GEOCHEMICAL ANALYSTS
METALLURGISTS

2095 WEST TRANS CANADA HIGHWAY — KAMLOOPS B.C.
V1S 1A7

PHONE: (604) 372-2784 — TELEX: 048-8320

CERTIFICATE OF ASSAY

TO Cyprus Anvil Mining Corporation Ltd.

Certificate No. K-4206 18

Date August 31, 1981

REVISED


December 6, 1984

I hereby certify that the following are the results of assays made by us upon the herein described Vangorda samples

Kral No.	Marked	Au	Ag	Cu	Fe	Py	As	S.G.	BaO	Po
		grams per tonne	grams per tonne	percent	percent	percent	percent		percent	percent
341	6010	.21	54	.05	13.2	11.5	.02	3.69	13.4	1.7
342	6011	.07	20	.06	11.2	8.4	.05	3.18	4.6	2.8
343	6012	.75	36	.13	22.9	17.7	.07	3.80	6.4	5.2
344	6013	.41	31	.25	35.5	29.9	.07	4.26	1.3	5.6
345	6014	.48	39	.15	32.8	28.1	.03	4.46	4.5	4.7
346	6015	.75	46	.17	23.1	21.4	.05	4.05	11.7	1.7
347	6016	.27	25	.27	31.1	29.3	.10	3.91	.7	1.8
348	6017	.27	25	.28	27.7	25.3	.03	4.02	1.0	2.4
349	3909	.48	34	.16	21.5	12.5	.03	3.61	.3	9.0

L means "Less than"

NOTE:
Rejects retained three weeks.
Pulps retained three months
unless otherwise arranged.



Registered Assayer, Province of British Columbia