



WHITEHORSE ASSAY OFFICE  
 BOX 4518  
 WHITEHORSE, YUKON

Samples from: CYRUS-ANUIK

Lot. No.: A-840-84

ROCK GEOCHE MS.  
 ALL RESULTS - P.P.M.

SAMPLE #	Pb	Zn	SAMPLE #	Pb	Zn	
140-150	264	1280	75-0-2 299-304	8	40	✓
150-160	116	168	319-324	280	88	✓
160-170	168	120	340-345	60	72	✓
170-180	124	112	345-350	72	88	✓
180-190	96	144	380-385	320	144	✓
190-200	108	40	385-390	260	256	✓
200-210	192	96	390-395	276	200	✓
210-220	116	56				
			75-0-3 85-90	392	13200	✓
20-30	160	312				
30-40	760	256	75-T-1 135-140	1240	4416	✓ #2
40-50	304	328	165-170	620	9856	✓
50-60	188	616	175-180	156	30912	✓
60-70	104	552	410-415	240	224	✓
70-80	80	728	415-420	76	264	✓
80-90	104	240				
90-100	244	800	75-T-2 35-40	500	2400	✓
100-110	52	160	45-50	108	880	✓
110-120	68	416	115-120	540	2208	✓
120-130	228	1968	110-115	1080	4512	✓
130-140	80	592	120-125	1020	3360	✓
220-230	56	48	125-130	560	1968	✓
230-240	84	96	130-135	940	2496	✓
240-250	124	152	140-145	1100	3648	✓
250-260	64	56	145-150	124	816	✓
260-270	48	48	150-155	900	12672	✓
270-280	64	24	260-265	440	13024	✓
280-290	76	64	320-325	120	27888	✓
290-300	24	24	325-330	144	12672	✓
300-310	32	40	450-455	264	4656	✓
310-320	104	40	460-465	52	15792	✓
320-330	40	16	465-470	44	5184	✓
330-340	24	68				
340-350	36	56				
350-360	72	40				
360-370	56	32				
370-380	40	56				
380-388	52	112				

RESULTS  
 O.K.

Date: August 19, 1975

Assayer: K. Hoyland



