

DATE. MAY 8, 1974.

ASSAY CERTIFICATE

FILE NO. 8138-19

WHITEHORSE ASSAY OFFICE LTD.
BOX 4518 WHITEHORSE Y.T.

018821

PHONE 667 2694

SAMPLE RECEIVED FROM

AEX MINERALS CORPORATION

A-5

SAMPLE NO.	GOLD Oz. Per Ton	SILVER Oz. Per Ton	LEAD	ZINC	COPPER	Feasible	
740001 ✓ <i>L</i>	.01	3.84	10.6	9.62	.20	420-210	- 6 of 0.02
740002 ✓ <i>4.5</i>	TR	.12	.68	1.80	.04	508-5125	} 18.5' - Nitrate
740003 ✓ <i>4.5</i>	TR	.08	.15	.38	.02	- 570	
740004 ✓ <i>4.5</i>	TR	.04	.25	.24	.06	5215	
740005 ✓ <i>5.0</i>	.01	.36	1.03	1.44	.07	5265	
740006 ✓ <i>5.0</i>	.01	3.32	6.5	21.5	.25	530.5	
740007 ✓ <i>6.5</i>	.01	1.72	4.7	22.9	.16	537.0	} 60ft - 0.02", 2.70", 5.29", 11.42", 0.20"
740008 ✓ <i>5.5</i>	.02	5.14	9.2	15.5	.32	542.5	
740009 ✓ <i>2.0</i>	.01	.28	.38	.38	.06	542.5	
740010 ✓ <i>1.8</i>	.02	1.78	3.98	8.06	.05	542.5	
740011 ✓ <i>10.2</i>	.005	.08	.38	.62	.06	542.5	
740012 ✓ <i>2.8</i>	.02	2.26	4.05	6.85	.19	559.3	
740013 ✓ <i>4.2</i>	.02	3.06	6.45	12.3	.16	563.5	
740014 ✓ <i>4.5</i>	.04	4.44	6.60	13.1	.28	568.0	
740015 ✓ <i>3.9</i>	.04	4.36	5.78	9.24	.29	571.9	
740016 ✓ <i>5.1</i>	.04	2.40	5.85	9.03	.33	577.0	
740017 ✓ <i>4.0</i>	.04	4.12	6.90	9.1	.34	581.0	
740018 ✓ <i>5.5</i>	.02	3.66	9.2	17.4	.18	581.5	
740019 ✓ <i>5.3</i>	.01	.48	1.13	2.28	.05	591.8	

ASSAYER: *K. Hayward for H. Holding*

DATE. MAY 8, 1974.

ASSAY CERTIFICATE

FILE NO. 0138-19

WHITEHORSE ASSAY OFFICE LTD.
BOX 4518 WHITEHORSE Y.T.

PHONE 667 2694

A-5

SAMPLE RECEIVED FROM

AEX MINERALS CORPORATION

SAMPLE NO.	GOLD Oz. Per Ton	SILVER Oz. Per Ton	LEAD	ZINC	COPPER	Footage	
740001	.01	3.84	10.6	9.62	.20	420-426	
740002	TR	.12	.68	1.80	.04	508-512.5	
740003	TR	.06	.15	.38	.02	512.5-517	
740004	TR	.04	.25	.24	.06	517-521.5	
740005	.01	.36	1.03	1.14	.07	521.5-526.5	
740006	4' .01	3.32	6.5	21.5	.25	526.5 - 530.5	1.5' barren
740007	6.5' .01	1.72	4.7	22.9	.16	530.5 - 537	
740008	6.0' .02	5.14	9.2	15.5	.32	537 - 543	10.3' barren
740009	1.5' .01	.28	.38	.38	.06	543 - 544.5	
740010	1.75' 2.75 .02	1.78	3.98	8.06	.05	544.5 - 546.25	
740011	.005	.08	.38	.62	.06	546.25 - 556.5	
740012	2.8 .02	2.26	4.05	6.85	.19	556.5 - 559.3	
740013	4.7 .02	3.06	6.45	12.3	.16	559.3 - 563.5	
740014	4.5 .04	4.44	6.60	13.1	.28	563.5 - 568	
740015	3.8 .04	4.36	5.78	9.24	.29	568 - 571.8	
740016	5.2 .04	2.40	5.85	9.03	.33	571.8 - 577	
740017	7.0 .04	4.12	6.90	9.1	.34	577 - 581	
740018	5.5 .02	3.66	9.2	17.4	.18	581 - 586.5	
740019	30.0 .01	.48	1.13	2.28	.05	586.5 - 591.7	

Arithmetic Averages - not weighted on sample length.

6' Sections 420 - 426 3.84 Ag 10.6 Pb 9.62 Zn .20 Cu Ag/Pb .36

19.7' Section excl. 1.5' barren 526.5 - 546.2 .015 Au 3.0 Ag 6.0 Pb 17.2 Zn .20 Cu Ag/Pb .5

30' Section 556.5 - 586.5 .03 Au 3.5 Ag 6.7 Pb 11.5 Zn .25 Cu Ag/Pb .54

56' total - got stuck, ~~probably~~ ^{maybe} did not penetrate whole zone.

23.2
18.2
50% of 20.7% comb. = 3.2 oz Au
+ 6' 20% comb = 3.8 oz Au

ASSAYER: *Richard H. Harding*

ASSAY CERTIFICATE

WHITEHORSE ASSAY OFFICE LTD.
BOX 4518 WHITEHORSE Y.T.

PHONE 667 2694

DATE. MAY 31, 1974.

FILE NO. 8167-26 & 8171-14

SAMPLE RECEIVED FROM

AEX MINERALS CORPORATION

SAMPLE NO.	GOLD Oz. Per Ton	SILVER Oz. Per Ton	LEAD	ZINC	COPPER				
301 306.75-312.5 (5.75')	.01	1.08	2.03	4.08	.03				
301 306.75-318 (5.5')	.01	.92	2.48	4.62	.03				
302 318-322 (4')	.005	1.16	3.08	6.48	.04				
302 318-324.5	.01	.84	1.93	2.28	.06				
303 238-245	.01	.40	.98	1.12	.04				
303 238-250	.01	.48	.90	1.26	.06				
304 250-263	.005	.32	.80	.90	.07				
304 250-267	TR	.08	.21	.08	.04				
305 583.5-592.5	.01	1.48	3.23	6.11	.05		3.23	6.11 1.49	
306 373.75-378.75 (4.9')	.01	.64	1.18	3.36	.09	5'		9.0'	
306 378.75-383.75	.005	.32	.95	2.28	.03	5'			
307 383.75-388.75	.02	1.82	2.23	5.28	.03	5'			
307 388.75-393.75	.01	1.67	2.50	5.40	.04	5'	2.25	4.06 1.53	
308 393.75-398.75	.01	1.12	2.03	4.20	.05	5'		15'	
309 398.75-403.75	.01	.56	.98	1.40	.03	5'			
310 403.75-408.75	.01	.80	2.00	4.02	.06	5'	4.10	6.32 2.04	
311 410-416	.02	2.90	5.55	7.92	.06	6'		12.25	
312 414-419	.01	1.68	2.85	6.12	.08	5'			
313 439-444	.04	2.80	5.55	10.52	.12	5'			
314 444-449	.02	2.78	7.50	10.63	.09	5'	4.32	7.82 2.25	
315 449-454	.03	3.01	7.35	11.88	.10	5'		45.0'	
316 454-459	.02	2.18	2.45	5.16	.05	5'			
316 459-464	.02	1.62	1.90	4.26	.04	5'			
317 464-469	.02	1.50	2.93	7.08	.05	5'		13.4	
318 469-474	.02	2.86	4.28	8.50	.10	5'			
319 474-479	.02	1.82	4.13	6.24	.07	5'			
8171-14: A10									
2520	.005	.24	.18	1.58	.03				
2521	.02	3.06	5.55	14.79	.24	518.5-523.5 (5.0')			
2522	.02	2.14	4.35	6.96	.14	-528.5 (5.0')			
2523	.04	1.56	2.55	2.76	.24	-533.5 (5.0')			
2524	.04	1.48	3.08	4.26	.28	-538.5 (5.0')	4.34	8.73 2.21	
2525	.04	3.12	6.38	11.45	.10	-543.5 (5.0')		35'	
2526	.02	2.82	5.63	13.50	.10	-548.5 (5.0')			
2527	.01	1.32	2.85	7.44	.04	-553.5 (5.0')			
2528	.02	1.22	1.08	2.58	.27	-558.5 (5.0')			
2529	.04	2.68	3.83	7.20	.13	558.5-563.0 (4.5')			
2530	.04	4.48	7.65	13.86	.29	-568.5 (5.0')			
2531	.06	3.86	8.70	16.97	.22	-573.0 (5.0')			
2532	.02	3.18	7.80	14.04	.15	-578.0 (5.0')			
2533	.02	1.90	4.35	9.68	.07	-583.0 (5.0')			

ASSAYER.

see next page for weighed an.

DATE. JUNE 10, 1974.

ASSAY CERTIFICATE

FILE NO. 6194-25

WHITEHORSE ASSAY OFFICE LTD.
BOX 4518 WHITEHORSE Y.T.

PHONE 667 2694

SAMPLE RECEIVED FROM

AMX MINERALS CORPORATION

SAMPLE NO.	GOLD Oz. Per Ton	SILVER Oz. Per Ton	LEAD	ZINC	COPPER	SPECIFIC GRAVITY		
2534	.01	.60	1.63	3.48	.03	583 - 593.0	(10.0')	
2535	.01	1.04	3.15	5.64	.04	-603.0	(10.0')	468.6, 95, 189
2536	.02	1.50	5.25	3.96	.10	-613.0	(10.0')	64.5'
2537	.02	1.10	4.20	1.24	.08	-623.0	(10.0')	
2538	.01	.24	.65	.28	.09			
2539	.01	.32	.73	.10	.14			
2540	.005	.24	.50	.42	.10			
2541	.005	.16	.35	.74	.07	-653-678 (25')		
2542	.02	.66	1.80	2.40	.09	-678-686.5 (2.5')		
2543	.01	.59	.80	1.44	.15	-616.5-690 (3')		
2544	.02	1.02	2.33	3.66	.10	-690-700 (10')		
2545	.01	.20	.44	.58	.13	-700-710 (10')		
2546	.01	.75	1.85	2.92	.16	-710-720 (10')		
2547	.01	.24	.10	1.32	.17	720-725 (5')		
2548	.02	.54	.70	1.16	.31	725-730 (5')		
2549	.04	3.44	7.35	11.61	.13	730-735 (5')		
2550	.04	2.84	4.95	7.20	.22	-740 (5')		
2551	.04	3.16	5.80	7.63	.23	-745 (5')		5.14 8.03 2.63
2552	.04	2.56	5.10	9.52	.31	-750 (5')		26'
2553	.02	1.18	2.50	4.20	.13	750-756 (6')		
2554	.02	1.82	3.00	6.72	.06	767-775.4 (8.4')		3.0 6.72 1.82
2555	.02	1.02	2.73	3.12	.05	779-783 (4.0')		8.4'
2556	.04	2.80	5.25	13.80	.18	785-787.6 (2.6')		
2557	.04	2.40	5.25	7.44	.20	802-808.5		4.5 6.27 2.24
2558	.02	2.68	3.75	5.10	.19	* -815		13'
							To Follow	

3.6' x 11.6
7.1 x 4.8
2.6' x 17.0
19.2
47.4
268.6
1.5%

ASSAYER: *K. Hayward for H. Spalding*

June 13

Average Core A10

Sirola

Today: Ph 30 Cu 29 Ag 29 Pb 29

518-573 (55') 4.7 9.25 0.19 2.52 0.03

573-623 (50') 4.07 5.24 0.07 1.37 0.02

518-623 Avg 4.39 6.75 .13 1.95 0.03
App

623-653 (30') 1.88 2.58 0.33 0.20 0.025

653-718 (25') 0.35 0.74 0.07 0.16 0.015

2542 678-686.5 (8.5') 1.89 2.42 0.09 0.66 0.02

2543 686.5-690 (3') 0.2 1.44 0.15 0.57 0.01

2544
2545
2546 690-720 (30') 1.54 2.25 0.11 0.66 0.01

2547
2548 720-730 (10') 0.4 1.24 0.24 0.39 0.02

2549
2553 730-756 (26') 5.14 8.03 0.20 2.63 0.04

2554 767-775.4 (8.4') 3.0 6.72 0.06 1.82 0.02

2555 779-783 (4') 1.73 3.12 0.05 1.02 0.02

2556 785-787.6 (2.6') 5.25 13.5 0.18 2.80 0.04

2557
2558 802-815 (13') 4.5 6.27 0.19 2.24 0.03

OB → 106'
133 - 219
Kept 171-178
(Barren)
matte HG
(80' total)

A13

June 19

A-12 1045-55 "massive high grade"
1104 end.

A-13 404-410 Some 5-6' HG
Some min from 308 down to 410
428-509 mineralized graphite phyll ? 2%
→ pale chloritic phyll.
611 end.

92W 10N, 76W 3S

A-11 ✓

DATE. JUNE 16, 1974.

FILE NO. 8222- 14

ASSAY CERTIFICATE

WHITEHORSE ASSAY OFFICE LTD.
 BOX 4518 WHITEHORSE Y. T.
 PHONE 667 2694 Y1A 2R8

SAMPLE RECEIVED FROM

ABX MINERALS CORPORATION

SAMPLE NO.	GOLD Oz. Per Ton	SILVER Oz. Per Ton	LEAD	ZINC	COPPER			
2559 *	.02	2.70	6.00	6.04	.12	—	579 - 387	8'
2560	.01	1.28	2.10	2.50	.15	—	390.5 - 28.5	
2561	.01	1.12	1.95	1.26	.21	—	340.5 - 402.5	
2562 *	.005	.20	.53	.40	.07	—	410.5 - 219	
2563	TR	.46	1.30	.58	.08	—	437 - 441	
2564 *	TR	.22	.28	.27	.03	—	432 - 253.5	
2565	.01	.96	4.00	3.04	.15	—	493.5 - 500	6.5'
2566	.005	.78	4.20	3.90	.20	—	500 - 506.5	
2567	.04	3.28	6.00	9.40	.15	—	584 - 591.5	7.5'
2568 *	.04	4.56	8.74	13.50	.20	—	591.5 - 599 15	7.5'
2569	.02	1.33	2.40	2.70	.27	—	693 - 704	7'
2570	.01	.70	.33	.54	.12	—	700 - 704	
2571 *	.01	.92	.08	.66	.15	—	728 - 736.5	
2572	.01	1.92	3.38	5.20	.13	—	736.5 - 745	4.5'

* Two bags with same number - Samples were mixed together.

ASSAYER K. Heyland for G. Spalding

DATE. 10/2/54

FILE NO. 8277-25

2571-2578

A-12

ASSAY CERTIFICATE

WHITEHORSE ASSAY OFFICE LTD.
BOX 4518 WHITEHORSE Y.T.

PHONE 667 2694

SAMPLE RECEIVED FROM

ABX Minerals Corporation

SAMPLE NO.	GOLD Oz. Per Ton	SILVER Oz. Per Ton	LEAD	ZINC	COPPER			
2579	TR	.30	.30	.58	.05	745-755 (10)		5.33, 7' 0.126
2580	.01	1.26	2.33	7.80	.04	-763 (8)		8'
2581	.01	.90	2.00	2.70	.04	811-821 (10)	} 2.00, 3.08, 1.10	30'
2582	.01	1.30	2.45	3.06	.07	-831 (10)		
2583	.01	1.12	2.35	3.43	.05	-841 (10)		
2584	TR	.04	.45	.26	.06	-852.5 (10.5)		
2585	.005	.64	1.20	2.40	.05	875-905 (10)		
2586	.005	.38	.73	1.76	.05	-915 (10)	40' ?	
2587	.02	1.40	2.18	3.90	.13	-925 (10)		
2588	.02	.64	1.13	1.68	.09	-935 (10)		
2589	.005	.44	.25	.22	.07	-945 (10)		
2590	.02	.88	1.25	1.62	.15	-955 (10)		
2591	.01	.94	1.00	.80	.19	-965 (10)		
2592	.02	.76	1.03	.60	.19	-975 (10)		
2593	.02	.82	1.45	2.40	.13	-985 (10)		
2594	TR	.12	.48	.38	.09	-995 (10)		
2595	.02	.96	1.00	.90	.13	-1005 (10)		
2596	.02	1.54	1.45	.20	.21	-1015 (10)		
2597	.02	.72	.80	.54	.12	-1025 (10)		
2598	.01	.76	.10	.23	.22	-1035 (10)		
2599	.02	.48	.10	.19	.15	-1044.5 (9.5)		1.73 6.96, 2.80
2600	.02	2.80	4.73	6.86	.25	-1054.5 (10)	✓	10
2601	.01	.76	1.25	.62	.21	133.5-145.5 (12)		7.88 6.96, 2.9
2602	.04	3.12	8.10	8.40	.16	145.5-158.5 (13)		26'
2603	.05	2.70	7.65	5.52	.19	158.5-171.5 (13)		
2604	.02	2.68	5.03	4.20	.21	180-193.5 13.5	5.03, 4.20, 2.6	
2605	.005	0.80	1.50	1.90	.15	-197.0 3.5	13.5	
2606	.04	2.08	5.25	5.40	.20	-202.0 5.0	5.25, 5.40, 2.08	
2607	.03	0.99	1.25	0.16	.08	-210.5	5.0	
2608	.02	1.56	1.63	0.90	.20	-219.0		
2609	.01	0.72	0.90	2.00	.03	398-404.0 6.5	3.23, 4.74, 1.98	
2610	.02	1.98	3.23	4.74	.15	-410.5 6.5	6.5	
2611	.01	0.56	0.80	1.50	.09	428-448		
						793.5-		

ASSAYER. *K. Hayward for H. Spalding*

RECEIVED

JUL - 9 1974

KERR ADRIAN MINES LTD.

PER

DATE. JULY 7, 1974.

FILE NO. 8311-15

ASSAY CERTIFICATE

WHITEHORSE ASSAY OFFICE LTD.
 BOX 4518 WHITEHORSE Y. T.
 PHONE 667 2694 Y1A 2R8

SAMPLE RECEIVED FROM

AEX MINERALS CORPORATION

SAMPLE NO.	GOLD Oz. Per Ton	SILVER Oz. Per Ton	LEAD	ZINC	COPPER			
A-15 2612	.005	.66	1.90	1.16	.36	424.4-433.7		
2613	.01	1.44	3.00	3.00	.03	453.0-463.5	10'	
2614	.01	3.66	6.00	4.02	.05	473	10'	
2615	.01	1.78	3.38	3.43	.05	485	10'	3.63 3.97, 2.13
2616	.01	2.56	5.13	7.44	.03	489.5	6.5'	49.0'
2617	.005	1.44	3.15	3.43	.07	493.0	3.5'	
2618	.01	1.63	5.40	3.18	.03	497.0	4.0'	
2619	.005	1.40	3.60	3.54	.06	522.0	5.0'	
2620	.005	.44	1.50	2.22	.03	520-560		
2621	.01	1.02	1.98	3.84	.03	560-570	10'	2.79 4.71, 1.20
2622	.01	1.42	3.60	5.58	.04	580	10'	20'
2623	.01	.66	1.83	2.40	.05	592		
2624	.01	.00	2.40	3.42	.04	600		
2625	.01	.88	1.93	2.88	.04	610		
2626	.005	.72	1.40	2.70	.06	623		

ASSAYER. K. Hoyland for G. Spalding

A-14

DATE. July 10, 1974

FILE NO. 8325-8

ASSAY CERTIFICATE

WHITEHORSE ASSAY OFFICE LTD.
BOX 4518 WHITEHORSE Y. T.
PHONE 667 2694 Y1A 2R8

SAMPLE RECEIVED FROM

ALX MINERALS

SAMPLE NO.	GOLD Oz. Per Ton	SILVER Oz. Per Ton	LEAD	ZINC	COPPER			
<i>A-14</i> 2627	.01	.64	1.45	1.22	.19	630-636		
2628	.005	.92	.29	.42	.16	873-883		
2629	.005	1.08	.63	.69	.16	883-896		
2630	.02	2.67	6.53	6.96	.30	896-905	→ 6.53, 6	2.67
2631	.005	.36	.55	.66	.20	905-915		9.0
2632	.01	1.56	2.00	2.76	.17	915-925		
2633	.01	.64	.33	.46	.15	925-930		
2634	.005	.96	1.73	2.00	.20	930-942		

ASSAYER. Geo. Spalding

A-16

RECEIVED

KERR ADDISON MINES LTD.

REF

DATE. JULY 17 1974.

FILE NO. 8360-13

ASSAY CERTIFICATE

WHITEHORSE ASSAY OFFICE LTD.
BOX 4518 WHITEHORSE Y. T.
PHONE 667 2694 Y1A 2R8

SAMPLE RECEIVED FROM

ABX MINERAL CORPORATION A-16

SAMPLE NO.	GOLD Oz. Per Ton	SILVER Oz. Per Ton	LEAD	ZINC	COPPER		FTx Pb	FTx Zn
2635 ✓	.005	.66	.68	.78	.03	644-666		
2636	.01	.60	1.19	1.72	.03	677-693		
2637	.005	.34	.20	.16	.04	761-771		
2638	.02	.28	.09	.01	.02	-781		
2639	.01	.28	.05	.02	.02	791		
2640 ✓	.005	.34	.07	.02	.02	801		
2641 ✓	.01	.52	.64	1.12	.02	811		
2642	.005	.24	.13	.10	.02	834-844		
2643 ✓	.005	.12	.09	.04	.02	849-857		
2644 10'	.01	.96	2.30	4.90	.03	861-871	10' 23.00	49.80
2645 12'	.02	1.24	2.35	3.18	.05	871-888	12' 20.05	54.76
2646 3'	.02	.92	1.58	3.24	.04	888-891	3 4.74	9.72
2647 12'	.005	.62	1.42	3.18	.03	891-903	12 17.04	38.16
							9083	151.94
					Pv	861-903=47	2.02 Pb	3.62 Zn
								0.97 Ag

10
 9.60
 19.15
 2.76
 7.44
38.95 = 0.9312.
 -72

ASSAYER. K. Heyland for H. Spalding

A-17

ASSAY CERTIFICATE

WHITEHORSE ASSAY OFFICE LTD.
BOX 4518 WHITEHORSE Y.T.

PHONE 667 2694

DATE. JULY 21, 1974.

FILE NO. 0376-20

SAMPLE RECEIVED FROM

IBX MINERAL CORPORATION

SAMPLE NO.	GOLD Oz. Per Ton	SILVER Oz. Per Ton	LEAD	ZINC	COPPER			
2648	.005	.78	1.90	1.54	.15	689-710		
2649	.005	.18	.34	.26	.07	- 710		
2650	.01	.80	1.03	1.40	.25	- 720		
2651	.005	.76	1.70	1.42	.24	- 728		
2652	.005	.92	1.08	1.18	.17	745-753		
2653	.005	1.00	2.00	1.58	.30	761-770		
2654	.01	.32	.30	.30	.22	778		
2655 ✓	.03	2.56	6.30	7.02	.23	778-784	→ 6.38, 7.92, 2.57	6.0
2656	.005	.48	1.03	.65	.10	786-792		
2657	.005	.80	1.03	1.00	.10	797		
2658	.04	1.32	3.15	5.04	.21	797-802	→ 5.04, 3.15, 1.32	5.0
2659	.005	.14	.25	.16	.17	807		
2660	.005	.18	.50	.66	.13	812		
2661	.02	.52	.98	1.52	.22	817		
2662	.005	.52	.28	.12	.24	822		
2663	.02	1.40	2.50	1.04	.23	827		
2664	.005	.80	1.05	1.26	.20	832		
2665	.01	.68	1.20	.51	.30	837		
2666	.01	.68	1.43	.66	.33	842		
2667	.005	.58	1.30	.61	.25	848		

ASSAYER. K. Hoyland for H. Spalding

RECEIVED

AUG - 1 1974
KERR ADDISON MINES LTD.

PER _____

DATE. JULY 23, 1974.

FILE NO. 8397-17

ASSAY CERTIFICATE

WHITEHORSE ASSAY OFFICE LTD.
BOX 4518 WHITEHORSE Y. T.
PHONE 667 2694 Y1A 2R8

SAMPLE RECEIVED FROM ARK MINERALS CORPORATION

SAMPLE NO.	GOLD Oz. Per Ton	SILVER Oz. Per Ton	LEAD	ZINC	COPPER			
A-20 001/	.02	2.84	6.08	11.96	.34	1021-1026	5'	5.64, 9.74, 3.16 22'
002/	.04	3.40	5.10	9.53	.34	1030	4'	
A-18 003/	.05	3.15	5.48	9.24	.29	1035	5'	
004/	.05	3.55	6.45	10.11	.20	1040	5'	
005/	.04	2.76	4.43	6.48	.17	1043	3'	
006/	.02	.94	1.85	2.28	.08	1049-1052	3'	5.01, 8.17, 2.91 9'
007/	.06	3.46	6.38	11.54	.11	1057-1062	5'	
008/	.02	1.96	3.30	4.98	.09	1066	11'	
009/	.02	1.12	2.78	3.84	.06	1071-1076	5'	4.16, 7.54, 2.88 16'
010/	.02	.90	1.58	3.06	.04	1081	5'	
011/	.02	.70	1.50	2.53	.05	1086	5'	
012/	.01	.76	1.38	2.70	.05	1092	6'	
013/	.005	1.32	1.40	3.60	.03	-1097	5A	
014/	.02	2.30	2.20	4.74	.11	1097-1103	6'	
015/	.04	3.36	5.93	10.92	.21	1103-1108	5'	
016/	.02	3.12	4.73	7.32	.25	1108-1113	5'	
017/	.005	.24	.60	.87	.04	1113-1120	7'	

ASSAYER. Geo. Spadney

Copy to Toronto Aug 1/74

ASSAY CERTIFICATE

WHITEHORSE ASSAY OFFICE LTD.
BOX 4518 WHITEHORSE Y.T.

PHONE 667 2694

DATE. JULY 28, 1971.

FILE NO. 8412-33

SAMPLE RECEIVED FROM

APX MINERAL CORPORATION

SAMPLE NO.	GOLD Oz. Per Ton	SILVER Oz. Per Ton	LEAD	ZINC	COPPER			
420-018 ✓	.005	.32	.43	.70	.04	603-607	4'	
-019 ✓ 6-87	.02	1.22	2.43	4.14	.10	613	6'	2.98, 119, 1.22
-020 ✓	.02	.02	1.73	3.06	.04	614-622	5'	6'
-021 ✓	.02	1.26	3.38	2.46	.08	627	5'	
-022 ✓ 6-86	.01	1.64	2.50	3.54	.04	632	5'	2.67, 60, 1.19
-023 ✓	.01	1.04	2.05	5.52	.06	637	5'	20.0'
-024 ✓ 6-67	.01	.80	1.80	2.88	.03	642	5'	
-025 ✓ 11-70	.01	.60	.90	1.76	.04	647	5'	
-026 ✓ 3-87	.005	.40	.88	1.66	.03	652	5'	
-027 ✓ 15-87	.005	.44	.98	.74	.04	657	5'	
-028 ✓ 4-27	.01	.44	.68	.66	.08	662	5'	
-029 ✓ 1-5-87	.01	.44	1.95	.66	.08	664	5'	
-030 ✓ 1-7-87	.02	1.46	3.15	4.50	.17	667-672	5'	4.08, 60, 1.83
-031 ✓	.02	2.28	5.25	8.04	.04	678	2'	9.0'
-032 ✓	.02	2.12	4.35	6.72	.05	689-693	4'	4.35, 1.72, 2.12
-033 ✓	.005	.50	.28	.27	.05	698	5'	4'
-034 ✓	TR	.16	.30	.48	.07	703	5'	
-035 ✓	.02	1.78	3.23	4.98	.13	708-708	5'	
-036 ✓ 7-10	.02	2.72	5.10	9.24	.25	713	5'	
-037 ✓	.02	1.94	3.38	7.44	.04	718	5'	
-038 ✓ 10%	.02	1.46	2.85	6.72	.06	723	5'	3.15, 2.85, 1.64
-039 ✓	.02	1.62	3.15	7.44	.05	728	5'	35'
-040 ✓	.02	1.34	2.43	5.40	.04	733	5'	
-041 ✓ 6-8	.02	1.10	2.00	3.72	.06	738	5'	
-042 ✓ 4-6	.01	.56	.58	1.18	.06	743	5'	
-043 ✓	.01	1.08	1.48	2.58	.05	748-753	5'	
-044 ✓	.01	.84	1.53	3.24	.03	759	6'	
-045 ✓	.01	1.20	1.38	2.34	.07	778-783	5'	3.15, 5.28, 2.46
-046 ✓	.02	2.46	3.15	5.28	.10	788-787	6'	6.0'
-047 ✓	.02	2.22	5.55	7.44	.07	812-817	5'	4.36, 4.39, 1.95
-048 ✓	.02	2.26	4.50	3.48	.08	822	5'	
-049 ✓	.02	1.38	2.15	3.36	.05	826	4'	14.0'
-050 ✓	.01	.72	.98	1.74	.05	843-848	5'	

RECEIVED

WHITEHORSE ASSAY OFFICE LTD.

ASSAYER.

Geo. Spalding

Copy 5 Total 6 Aug 1/71

DATE. August 2, 1974

FILE NO. 052-45

ASSAY CERTIFICATE

WHITEHORSE ASSAY OFFICE LTD.
BOX 4518 WHITEHORSE Y.T.

PHONE 667 2694

SAMPLE RECEIVED FROM

KEBR ADDISON MINES

A-19

*703
1.50
2294*

SAMPLE NO.	GOLD Oz. Per Ton	SILVER Oz. Per Ton	LEAD	ZINC	COPPER		
051	.02	1.38	1.85	1.92	.22	3358-340-6	4.8
052	.005	.32	1.18	1.02	.13	3456	5.0
053 ✓	.02	3.18	6.68	5.64	.11	355	9.8
054	.005	.04	.05	.17	.02	322-326	4.0
055	.02	1.70	2.50	4.02	.14	452	6'
056	.02	.92	1.15	2.00	.17	458.1	6.1'
057	.01	.64	.30	.60	.34	4673	9.2'
058 ✓	.04	4.08	7.35	9.36	.07	4773	10'
059 ✓	.02	.42	.25	.82	.16	480	7.7
060	.01	1.00	2.28	1.60	.14	493.0	8.0
061	.01	1.76	4.95	6.96	.06	500.5	7.5
062	.01	.32	1.33	2.58	.11	507.2	6.7
063 ✓	.01	.28	.60	.33	.09	510.0	
064 ✓	.005	.29	.68	1.34	.04	521-527.4	
065	.02	1.70	2.25	4.68	.11	5313-537.0	5.7
066	.02	3.64	4.35	6.04	.23	540.0	3.0
067 ✓	.02	3.26	7.55	12.72	.21	543.0	3.0
068	.02	1.46	3.15	4.74	.11	547.0	4.0
069	.02	1.22	2.95	3.72	.11	552.0	5.0
070	.02	1.56	2.28	3.60	.10	557.0	5.0
071	.02	1.52	2.50	6.24	.10	560.0	5.0
072	.02	2.24	4.55	9.48	.18	567.0	5.0
073 ✓	.02	2.24	4.74	8.64	.25	572.0	5.0
074	.04	3.20	5.78	10.20	.17	577.0	5.0
075	.02	1.00	3.48	5.76	.05	577.7	2.7
076	.01	1.36	1.85	3.33	.03	582.3	5.6
077	.04	1.48	2.18	3.10	.09	601.6	1.7
078	.06	4.02	9.15	15.36	.20	637-647.0	10.0
079	.01	.20	1.90	2.88	.29	651.0	4.8
080 ✓	.04	2.64	5.70	9.40	.26	659.0	8.0
081	.04	1.48	2.70	3.30	.33	664.4	5.4
082	.02	1.63	2.93	4.14	.29	673.5	9.1
083	.01	.48	.08	.37	.42	683.0	
084	.02	.56	.35	1.50	.26	693.0	
085	.01	.44	.14	.35	.33	703.0	
086	.01	.32	.18	.19	.39	711.1	
087	.02	.98	2.65	4.02	.14	718.5	
088	.01	.24	.14	.62	.44	729.2	
089	.01	.24	.07	2.00	.26	744.3	
090 ✓	.005	.28	.10	3.60	.30	748.0	
091	.005	.28	.12	3.48	.43	758.0	
092	.02	.92	.92	1.40	.37	769.2	
093	.02	1.86	2.93	2.92	.23	774.3	
53 *	No Ticket	3.76	6.83	13.06	.35		
54 *	No Ticket	4.12	6.98	9.68	.10		

RECEIVE

AUG 12 1974
KEBR ADDISON MINES LTD.

PER _____

* Serious analysis investigate

ASSAYER. *K. Hayward for H. Spalding*

DATE. AUGUST 9, 1974.

FILE NO. 8159-57

A 21

ASSAY CERTIFICATE

WHITEHORSE ASSAY OFFICE LTD.

BOX 4518 WHITEHORSE Y.T.

PHONE 667 2694

SAMPLE RECEIVED FROM

KERR ADDISON MINES

SAMPLE NO.	GOLD Oz. Per Ton	SILVER Oz. Per Ton	LEAD	ZINC	COPPER			
094	TR	TR	.03	.10	.02	3284-3316	3.2	
095	.02	2.32	5.78	11.35	.03	3316-3396	8.7	35.78, 1135, 23
096	TR	TR	.10	.30	.02	3422	2.6	8.7
097	.02	4.36	8.25	11.53	.15	3472-3575	9.3	21.84, 748, 210
098	.005	.94	2.23	4.25	.03	3590	7.5	35.8
099	.01	1.64	4.43	8.76	.06	3686	9.6	
100	.01	1.16	3.75	7.44	.06	3730	4.4	
101	.01	1.36	4.20	7.50	.05	3780	5.0	
102	.005	.28	.88	1.74	.08	3760	-	
103	.005	.28	.84	1.68	.08			
104	.005	.32	.70	1.40	.10			
105	.005	.30	.63	1.26	.08			
106	.005	.34	.63	.95	.02			
107	TR	TR	.08	.33	.02			
108	.005	.66	1.65	3.24	.04		3.2	
109	TR	.26	.08	.10	.03	5945		
110	.01	1.24	2.43	4.74	.12	5945-6015	7.0	
111	.01	1.40	3.08	5.04	.09	6015-6080	6.5	
112	.01	1.52	2.50	4.20	.09	6130	5.0	
113 & 114 *	.02	2.08	4.43	8.76	.12	6130-6230	10.0	4.10, 768, 1.93
115	.02	2.24	4.28	9.12	.04	6330	10.0	615
116	.02	2.44	5.03	9.36	.17	6380	5.0	
117	.04	3.76	6.83	11.52	.17	6430	5.0	
118	.02	1.50	2.25	4.26	.15	6480	5.0	
119	.01	1.32	5.18	9.00	.12	6570	9.0	
120	.01	.15	.15	.23	.11			657.0, 564.1, 62.5
121	.005	.20	.42	.74	.07			
122	.01	.32	.98	1.58	.08			
123	.01	.48	.18	.51	.12			
124	.005	.24	.34	.29	.10			
125	.01	.16	.74	1.10	.06			
126	.01	.60	1.53	2.22	.06			
127	.01	.28	.23	.33	.13			
128	.01	.76	1.35	1.19	.16			
129	.01	.28	.15	.46	.22			
130	.01	.32	.10	.24	.18			
131	.005	.24	.18	.25	.18			
132	.01	.68	.89	1.08	.10			
133	.01	.72	1.25	1.54	.12			
134	.01	.28	.54	.78	.12			
135	.01	.16	.17	.28	.30			

* COMBINED ASSAY

RECEI

AUG 12 1974

KERR ADDISON MINES LTD.

ASSAYER. K. Howland for H. Spalding

A 21 + A 22 ?

ASSAY CERTIFICATE

DATE. AUGUST 9, 1974.

WHITEHORSE ASSAY OFFICE LTD.
BOX 4518 WHITEHORSE Y.T.

FILE NO. S150-57

PHONE 667 2694

SAMPLE RECEIVED FROM

KEIR ADDISON MINES

SAMPLE NO.	GOLD Oz. Per Ton	SILVER Oz. Per Ton	LEAD	ZINC	COPPER			
<i>A.21</i> 136	.01	.13	.88	.19	.17	789-799	10'	
137 ✓	.005	.23	.88	.56	.25	- 808	10'	
138 ✓	.01	1.12	1.93	2.62	.32	808-10-814-8	6.8'	
<i>A.22-7</i> 139 ✓	.01	.63	1.45	1.50	.44	506-507.6		
140	.005	.16	.75	.50	.18	571-576.5		
141	.01	.02	.23	.10	.07	- 586.3		
142	.01	.32	.78	.78	.27	5919-5938		
143	.02	2.30	5.53	5.52	.13	5928-6012	7.4 = 5.12, 6.05, 2.44	
144	.02	3.39	6.00	6.04	.16	6012	5.0	12.4
145	.005	.29	.76	1.16	.13	613.2		
146	.005	.83	.85	2.10	.21	619.0		
147 ✓	.02	1.72	4.35	8.50	.12	7512-7512	1.3.8	
148	.01	3.88	6.83	8.10	.27	- 7512	3.5	
149	.02	1.48	3.23	4.44	.15	- 757.0	5.5	= 3.5, 6.25, 1.88
150	.02	2.23	5.33	8.88	.09	777.0	10.0	
151	.02	1.40	2.35	5.16	.07	787.0	10.0	-1.8
152	.02	1.72	2.08	4.56	.06	- 796.0	9.0	

178
Copy sent to Toronto
Aug 16/74

RECEIVED

AUG 12 1974
KEIR ADDISON MINES LTD.

ASSAYER. *K. Hoyland for G. Spalding*

A 22

ASSAY CERTIFICATE

DATE. AUGUST 2, 1974.

WHITEHORSE ASSAY OFFICE LTD.
BOX 4518 WHITEHORSE Y.T.

FILE NO. 0463-20

PHONE 667 2694

SAMPLE RECEIVED FROM

KEPP ADDISON MINES

SAMPLE NO.	GOLD Oz. Per Ton	SILVER Oz. Per Ton	LEAD	ZINC	COPPER			
<i>A22</i> 152	.02	1.72	2.08	4.56	.08	7715-7711	9.0	
153	<.01	.68	1.93	3.06	.08	- 7725	1.9	
154	.005	.16	.23	.43	.08	7080	8.0	
155	.005	.60	.63	.25	.12	8700	3.9	
156	<.01	1.52	3.83	6.96	.10	8104	7.8	388,696,152
157	<.01	.48	.69	1.40	.28	7200	4.3	9.8
158	<.02	1.32	2.08	2.00	.31	8300	4.1	
159	<.02	1.82	4.35	8.15	.12	8286-8340	6.3	435,787,181
160	<.02	1.94	4.35	7.68	.21	8400	9.7	165
161	.02	4.44	6.68	11.45	.02	8876-8879	1.6	
162	TR	.20	.08	.10	.02	8980-9004	2.4	52
163	.02	.80	1.58	3.00	.04	- 9032	2.8	
164	<.02	2.76	6.60	12.67	.08	9032-9080	4.8	620,1250,324
165	<.02	3.72	6.00	11.92	.15	914	8.6	116
166	.005	.04	.05	.06	.03	- 9180	3.6	
167	.02	2.36	4.35	7.20	.10	11251-11317	6.6	
168	.02	2.68	6.08	10.65	.09	1123	1.5	
169	.02	1.28	3.53	6.36	.04	1120	6.8	447,760,225
170	.02	1.44	3.53	6.60	.04	1145	15.6	39.1
171	.02	2.92	4.68	7.80	.10	1155	10.0	
172		257	518	876		11642	3.6	

Copy sent to Y...
Aug 16/74

RECEIVED

WHITEHORSE ASSAY OFFICE LTD.

ASSAYER. *K. Hoyland for M. Spalding*

RECEIVED

ASSAY CERTIFICATE

DATE. AUGUST 20, 1974.

AUG 22 1974

KERR ADDISON MINES LTD.

WHITEHORSE ASSAY OFFICE LTD.

FILE NO. 8517-49

BOX 4518 WHITEHORSE Y.T.

PER

PHONE 667 2694

A-23

SAMPLE RECEIVED FROM

KERR ADDISON MINES (Received Aug. 17 1974)

SAMPLE NO.	GOLD Oz. Per Ton	SILVER Oz. Per Ton	LEAD	ZINC	COPPER			
A-23 317✓		.06	.03	.03	.16	728-736	8'	
318✓		1.76	4.80	6.48	.09	722.5-722.5	7 @ 480, 0.48, 174	
319✓		1.59	3.38	3.48	.30	785.5-785.5	6.5	
320✓		1.00	2.20	1.10	.47	794-799	5.0	2.89 2.99, 1.36, 19.2
321✓		1.35	2.78	3.66	.27	-804.7	5.2	
322✓		.15	.32	.76	.10	-810	5.3	
327✓		.35	.73	.98	.18	862-866	4.0	
328✓		.53	.85	.58	.31	-870	4.0	
329✓		.32	.50	.60	.19	-876	6.0	
330		.62	1.43	1.08	.19	904.5-909.0	4.5	
331✓		.41	.82	.82	.17	913.5-921.5	7.0	
A-24 332✓		2.65	6.15	5.40	.13	258.7-466.0	9.9 @ 615	540, 265, 9.9
333✓		.59	1.25	.74	.17	-470.5	1.9	
334✓		1.8	.07	.08	.03	-474.9	4.4	
335✓		2.53	5.55	3.54	.15	-479.1	4.2 @ 535, 3.54, 2.53	4.2
336✓		.12	.18	.04	.03	-483.5	4.4	
337✓		2.85	7.20	6.12	.18	495.6	10.1 @ 700, 6.12, 2.85	
338✓		.27	.65	.60	.04	495.0	1.4	
339✓		.09	.70	1.50	.03	581.5-583.0	1.5	
340✓		.06	.08	.11	.03	-585.3	2.3	
341✓		3.56	7.20	12.3	.18	-586.0	2.7	
342✓		1.76	3.53	4.86	.13	-591.0	3.0	415 6.69, 1.96
343✓		1.03	2.13	3.72	.10	597	6.0	32.7
344✓		3.00	7.20	10.20	.12	-607	10.8	36.5
345✓		2.21	3.83	7.56	.20	-614.4	7.4	
346		1.09	2.40	4.50	.04	-618.0	3.6	
347		.47	.85	1.74	.04	620.5	2.5	
348✓		.15	.19	.50	.05	629.5	9.0	
349✓		3.24	8.25	14.63	.13	-637	7.5	
350		1.88	4.13	7.92	.21	645.3	6.3	
351		1.76	3.83	6.96	.10	648.3	5.0	469, 5.12, 1.66
352		1.09	2.35	5.64	.15	654.2	5.9	40.2
353		1.15	2.85	4.92	.05	659.6	5.0	
354		1.76	5.70	6.24	.08	666.5	6.9	
355		1.68	4.05	2.76	.15	669.7	3.2	
356		.41	.72	.63	.09	673.0	3.3	
357✓		.44	.73	.36	.15	682.8	9.8	
358✓		.35	.62	.82	.05	690.9	8.0	
359✓		.21	.30	.65	.10	698.9	8.0	
360✓		.83	1.95	3.42	.13	706.7	7.8	
361✓		.21	.49	.77	.10	711.0	7.3	
362✓		1.24	3.30	6.12	.08	716.6	5.6	
363		.44	1.65	2.34	.07	719.7	3.1	245 3.90, 0.95
364✓		.91	2.05	3.18	.15	726.0	6.3	22.0
365		.94	2.50	3.54	.12	732.0	6.0	
366✓		1.24	2.50	3.24	.10	733.0	1.0	
367✓		.44	.72	.98	.06	737	4.0	
368		.03	.03	1.08	.03	742	5.0	
369✓		.09	.25	.40	.02	743.5	1.5	

ASSAYER. K. Hayland for H. Spalding

DATE. AUGUST 25, 1974.

RECEIVED

ASSAY CERTIFICATE

FILE NO. 0563-26

179 - 331 AUG 27 1974

WHITEHORSE ASSAY OFFICE LTD.
BOX 4518 WHITEHORSE Y.T.

KERR ADDISON MINES LTD.

PHONE 667 2694

SAMPLE RECEIVED FROM DEP. KERR ADDISON MINES

SAMPLE NO.	GOLD Oz. Per Ton	SILVER Oz. Per Ton	LEAD	ZINC				
172 ✓		2.59	5.16	8.76	1155.6-11642	8.6		
173 ✓		.28	.30	.77	-1166.3	2.1		
174 ✓		2.56	4.58	7.80	1169.1	2.8	} 3.9' 120 6.59 2.10 3.9'	} 274 450 1.33 10.4'
175 ✓		.97	2.55	3.54	-1170.2	1.1		
176 *		.24	.47	.40	1171.2-1172.7	2.7		
177 ✓		1.88	3.08	5.28	1184.8-1188.0	3.8		
178 A-22		.03	.14	.12	-1191.8			
179 A-23		5.18	12.2	23.4	256-259	3'	} 6.49, 11.96, 2.99 25' (incl #323 3rd)	
180 ✓		2.41	5.40	10.5	266-272.5	6.5'		
181 ✓		.47	.48	.51	275-275.5	3.0		
182 ✓		1.71	4.28	7.08	285-281.5	5.5'		
183 ✓		.50	1.45	1.16	281-286.5	5.5'		
184 ✓		.41	.98	1.60	-292-304	12.0		
185 ✓		.27	.43	.87	-304-314	10.0		
186		.35	.75	1.12	-320	11.0		
187		1.18	2.85	4.86	325-331	6.5		
188		2.50	5.55	12.1	331-332.8	1.8		
189		2.06	4.50	9.00	337-347	10'		
190		1.47	2.93	8.16	347-356.5	9.5'		
191 ✓		2.21	4.50	9.48	354-369.3	5.3		
192		4.59	9.00	19.5	377-387	10'		
193		3.68	8.10	19.61	-397	10'		
194		4.41	9.60	19.0	-407	10'		
195-316 195		2.68	5.73	10.54	-415	8.0'		
317-321 322		5.15	11.2	21.1	259-263	4'		
323		3.09	7.35	12.41	-266	3'		
324		.32	.70	1.48	286.5-292	5.5'		
325		2.94	4.88	10.8	332.8-337	4.2		
326								

* Not received
956 Fred or Stan
Check log

TOTAL ORE SECTIONS
25'
82'
50'
157'

From 325-415
5.07, 9.88, 2.22
90'
From 432-462
5.02, 7.56, 2.05
30'

ORL

Samples received Aug. 20/74

ASSAYER. K. Hayward for H. Appalding

RECEIVED

ASSAY CERTIFICATE

DATE. AUGUST 25, 1974.

AUG 27 1974

WHITEHORSE ASSAY OFFICE LTD.

FILE NO. 8558-34

KERR ADDISON MINES LTD.

BOX 4518 WHITEHORSE Y.T.

PHONE 667 2694

PER KERR ADDISON MINES

SAMPLE RECEIVED FROM _____

SAMPLE NO.	GOLD Oz. Per Ton	SILVER Oz. Per Ton	LEAD	ZINC			
<i>A-24</i> 370 ✓		.29	.37	1.60	743.5	748.0	4.5
371		1.76	2.35	3.90	751.8	3.0	3.01
372		2.05	2.50	4.92	753.0	2.0	221,560,208
373		.09	.08	.34	754.0	1.0	100'
374		2.82	4.55	6.52	758	4.0	
375		.12	.13	.19	777	2.0	
376 ✓		.86	.85	.11	819	826.1	7.1
377 ✓		2.82	4.65	8.88	831.6	5.5	5.5 @ 465,886,282
378 ✓		.83	.85	.10	836.4	4.8	
379		1.03	1.28	2.28	844.2	7.8	
<i>A-26</i> 401		.74	1.55	3.34	153-163	10	
402		.83	2.30	5.16	-169	6.5	
403		.59	2.00	3.24	183-189.7	6.7	
404		2.74	4.13	9.96	189.7-195.0	5.3	
405		3.03	5.55	13.2	201.5	6.5	✓
406		3.82	7.80	17.55	203.6-209	5.4	✓
407 ✓		3.00	6.30	14.45	-214	5.0	✓
408		3.41	7.35	15.34	-223.2	9.2	✓
409 ✓		1.50	3.30	11.67	-228.5	5.3	✓
410 ✓		1.50	3.15	6.24	231-233.5	2.5	✓
411		.29	.53	1.44	-238.0	4.5	✓
412		1.85	3.68	8.04	238-241.7	7.7	565, 11.10, 283
413		3.09	6.60	16.3	-244.3	2.6	125.80'
414		.32	.69	1.00	246	1.7	
415		3.53	6.90	14.22	248-249.5	1.5	✓
416		3.24	6.53	13.92	254.5-264.5	10.0	✓
417 ✓		4.15	8.40	14.10	-268	3.5	✓
418		6.24	9.30	19.50	-271	3.0	✓
419		3.82	6.25	15.8	-281	10.8	✓
420		5.00	9.60	18.9	-289	8.0	✓
421		3.09	5.85	7.44	-299	10.8	✓
422		3.09	6.15	9.00	-304	10.0	✓
423 ✓		2.44	6.23	7.56	315.5	6.5	
424 ✓		.65	1.58	1.06	322.6	7.1	

TOTAL ORE SECTIONS IN A-24 =

36.5
40.2
22.0
48.6
147.3

Samples received Aug. 20/74

ASSAYER. K. Hayland for H. Spalding

DATE. AUGUST 28, 1974.

FILE NO. 8579-53

ASSAY CERTIFICATE

WHITEHORSE ASSAY OFFICE LTD.
BOX 4518 WHITEHORSE Y.T.

PHONE 667 2694

SAMPLE RECEIVED FROM

KERR ADDRESS MINES

SAMPLE NO.	GOLD Oz. Per Ton	SILVER Oz. Per Ton	LEAD	ZINC				
A-23 195 ✓		2.68	5.73	10.54	407-415	8.0		
196 ✓		.38	.37	1.32	-426	11.0		
197 ✓		.41	.28	1.26	-432	6.0		
198 ✓		1.09	2.93	6.12	432-439	7.0		
199 ✓		3.18	6.90	14.59	446	7.0	502	7.56 2.05
200 ✓		3.53	8.25	15.71	-432	6.0		30'
301		1.06	3.23	3.78	-462	10.0		
302		.38	.55	.76	-472	10.0		
303		.47	.89	2.00	482	10.0		
304		.35	.44	1.04	492	10.0		
305		.27	.20	1.38	502	10.0		
306 ✓		.18	.17	1.04	509	7.0		
307		.35	.29	.60	519	10.0		
308 ✓		.41	.17	.67	529	10.0		
309 ✓		.21	.27	.79	534	5.0		
310 ✓		1.91	3.83	4.56	538	4.0 ✓		
311 ✓		.85	1.45	.70	544	6.0		
312 ✓		.26	.14	.37	551	7.0		
313 ✓		.35	.08	.78	557.8	6.8		
314		.15	.05	.29	568.0	10.2		
315 ✓		.24	.22	.65	570.0	2.0		
316 ✓		1.03	2.18	2.94	578.0	8.0		
A-24 380 ✓		2.71	4.95	9.72	1078.8-1084.8	6.0		
381 ✓		3.30	7.80	16.97	-1091	6.2		
382		2.21	5.10	6.24	1101	10.0	6.10	10.59 2.91
383 ✓		3.24	7.20	12.1	-1108.5	7.5		7.85
384		2.47	5.78	9.72	1118.5	10.0		
385 ✓		3.28	6.30	11.37	1127.4	8.9		
386		.06	.08	.13	1132.4	5.0		
A-26 425 ✓		1.03	3.08	3.72	3226-330	7.4		
426		.18	.32	.74	-338.8	8.8		
427 ✓		.50	1.38	1.35	-344.5	5.7		
428 ✓		2.85	7.05	8.04	-348.5	4.0	3.10	4.55 1.28
429 ✓		.59	1.35	3.00	-357.5	9.0		13.0
430		.71	1.28	1.35	367.5	10.0		
431		.08	.18	1.20	377.5	10.0		
432 ✓		.32	.14	.92	-387.5	10.0		
433		.18	.07	.65	-397.5	10.0		
434 ✓		.41	.35	1.74	407.5	10.0		
435		.15	.01	1.34	417.5	10.0		
436 ✓		.21	.18	1.04	421.5	4.0		
437 ✓		1.88	3.98	4.20	425.0	3.5		
438 ✓		.83	1.50	1.43	432.5	7.5	3.08	2.88 1.41
439		1.21	2.33	2.40	442.0	10.0		41'
440		1.91	4.73	4.02	452.0	10.0		
441 ✓		1.41	3.08	2.88	462.0	10.0		

Samples received Aug. 23/74

ASSAYER. K. Heyland for H. Spalding

AUGUST 28, 1976.

ASSAY CERTIFICATE

NO. 8579-53

WHITEHORSE ASSAY OFFICE LTD.
BOX 4518 WHITEHORSE Y.T.

PHONE 667 2694

SAMPLE RECEIVED FROM

KERR ADOLPHSON MINES

SAMPLE NO.	GOLD Oz. Per Ton	SILVER Oz. Per Ton	LEAD	ZINC				
A26.								
442		.80	1.33	2.28	262-472	10.2	Pb	Zn Ag
443		1.35	3.00	3.54	-475	3.0	14.0	3.49 1.11
444		1.03	2.08	3.48	-4827	7.7		20.7
445		1.09	3.38	3.60	5955-601.4	5.9		
446		2.35	4.95	6.84	6846-687.5	2.9	3.7	4.65 1.74
447		.44	.47	.06	692.2	2.7		10.1
448		2.15	4.13	5.52	-6947	4.5		

ASSAYER.

K. Heyland for H. Spalding

RECEIVED

ASSAY CERTIFICATE

DATE. AUGUST 31, 1974.

SEP-6 1974

KERR ADDISON MINES LTD.

WHITEHORSE ASSAY OFFICE LTD.
BOX 4518 WHITEHORSE Y.T.

FILE NO. 854-36

PER _____

PHONE 667 2694

SAMPLE RECEIVED FROM

KERR ADDISON MINES

SAMPLE NO.	GOLD Oz. Per Ton	SILVER Oz. Per Ton	LEAD	ZINC			
4-27 449 ✓		1.03	1.90	2.82	5258-528	2.2	
450 ✓		1.11	2.50	4.50	-5315	5.5	P. Zn 17.
451 ✓		1.32	2.23	4.82	-542	10.5	260 484 150
452 ✓		1.38	2.78	4.92	-552	10.0	31.2
453 ✓		2.41	3.45	5.64	-557	5.0	
454 ✓		.77	1.63	3.24	651 -564	7.5	
455 ✓		.52	.93	.77	-574	9.5	
456 ✓		.47	1.34	.89	-583	9.0	
457 ✓		.77	2.00	2.15	-593	10.0	
458 ✓		.97	3.08	.88	6015	8.5	
459 ✓		.24	2.78	3.60	6058	4.3	
460 ✓		.35	.75	.84	6087	2.9	
461 ✓		.29	.42	.54	616	7.3	25 3.71 2.8 14.25
462 ✓		.29	.54	.86	626	10.0	
463 ✓		.29	.63	1.48	636	10.0	
464 ✓		.18	.43	1.14	6405	4.5	2.403
465 ✓		.63	1.24	1.96	6405 646	5.5	
466 ✓		.88	1.73	1.98	6535	7.5	4.05 10.2 1.94
467 ✓		1.94	4.05	10.2	6583	4.8	4.8
468 ✓		.41	.68	1.00	6683	10.0	
469 ✓		.15	.99	2.40	6683-6743	5.0	2.943/3.3
470 ✓		.59	1.33	2.88	6775	3.3	
471 ✓	4-8	1.03	2.35	3.86	686-696	10.0	
472 ✓	4-8	1.03	2.40	2.28	-706	10.0	
473 ✓	4-8	1.62	4.13	3.18	-713	7.0	
474 ✓	4-8	2.50	5.10	3.24	719	6.0	3.80 4.04 1.45
475 ✓	4-8	2.21	5.25	6.43	725	6.0	73.0
476 ✓	4-8	3.47	7.05	10.98	7317	6.7	
477 ✓	4-8	1.29	2.50	3.24	739	7.3	
478 ✓	<4	.53	1.05	2.22	749	10.0	
479 ✓	<4	1.09	2.70	3.42	759	10.0	
480 ✓	<4	.53	1.23	1.06	769	10.0	
481 ✓		.24	.80	.60	847-852	5.0	
482 ✓		.65	1.08	1.30	-862	10.0	
483 ✓		.83	2.20	1.72	872	10.0	
484 ✓		.88	1.83	2.40	882	10.0	

ASSAYER. *L. Hayward for H. Spalding*

RECEIVED

ASSAY CERTIFICATE

DATE. SEPTEMBER 3, 1974.

SEP-6 1974

WHITEHORSE ASSAY OFFICE LTD.

FILE NO. 8583-42

KERR ADDISON MINES LTD.

BOX 4518 WHITEHORSE Y.T.

PHONE 667 2694

SAMPLE RECEIVED FROM

ADDISON MINES

SAMPLE NO.	GOLD Oz. Per Ton	SILVER Oz. Per Ton	LEAD	ZINC				
A-27 485/		.91	2.23	2.34	882-892	10.0		
486/		.89	2.28	2.22	-902	10.0		
487/		.50	1.35	1.20	710-715	5.0		
488/		.97	2.33	3.04	-920	5.0		
489/		1.35	3.00	4.38	925	5.0		
490/		.64	.70	1.38	925	10.0		
491/		.70	1.35	1.34	9233	8.3		
492/		.83	.87	.16	1068-1075	2.0		
493		1.70	3.90	6.26	-1074	3.5		
494/		.15	.18	.38	1075-2	1.2		
495/		.77	1.73	2.46	1083.3	8.1		
496/		.21	.19	.27	10895	6.2		
497/		1.82	3.25	7.08	10925	10.0	4.09, 7.98	1.94
498/		2.05	4.73	8.08	11095	10.0	20.0	
499/		.91	1.93	3.00	11155	6.0		
500/		1.32	2.16	3.30	1124.5	9.0		
501/		.38	.17	.45	11290	5.5		
502/		1.47	3.15	4.62	1134.0	5.0		
A-28 ✓503		.44	.84	.04	166-167.5	1.5		
✓504		.41	.75	.80	279.3-281	1.7		
✓505		3.38	6.68	11.04	281-289	8	0.68 11.04 3.28	
✓506		.94	2.08	1.38	289-293	4.2	8.50	
✓507		3.36	6.68	10.20	293-295.9	3.7	2.93 6.01 2.08	
✓508		3.68	6.68	10.97	300.5-303.8	3.3	10.6	
✓509		.59	1.28	1.80	407-413	6.0		
✓510		.53	.85	1.12	-420	8.0		
✓511		.21	.40	.62	-431	10.0		
✓512		.59	.77	.65	439	8.0		
✓513		.27	.53	.66	628.3-641.3	6.0		
✓514		.15	.05	.03	702-703.1	1.1		
✓515		.47	.93	.77	707-4	2.3		
✓516		1.35	3.53	2.52	712.0	4.8		
✓517		.70	.83	.59	714.1	1.9		
✓518		.83	1.28	1.28	719.3	5.2		
✓519		1.53	3.75	3.00	727.0	7.7		
✓520		.88	1.50	.82	737.0	10.0		
✓521		1.30	2.65	3.24	747	10.0		
522		.41	.49	.91	749	10.0		
✓523		.15	.12	.09	796-800.5	4.5		
✓524		.03	.05	.08	816-821	5.0		
✓525		.53	1.02	1.08	8295-838	8.5		
✓526		.59	.75	.60	853.5-858.5	5.0		

local by A-28

Samples received by 22/7

ASSAYER.

K. Hayward for H. Spalding

DATE. SEPTEMBER 7, 1974.

ASSAY CERTIFICATE

647
606.9
62.7

FILE NO. 8612-55

WHITEHORSE ASSAY OFFICE LTD.
BOX 4518 WHITEHORSE Y.T.

PHONE 667 2694

SAMPLE RECEIVED FROM

KERR ADDISON MINES

SAMPLE NO.	GOLD Oz. Per Ton	SILVER Oz. Per Ton	LEAD	ZINC			
122 176		.24	.47	.40	11702-1177.9	2.7	
A30 1387		4.32	8.70	17.1	5742-477	2.8	
✓ 1388		.15	.23	.42	-480	3.0	
✓ 1389		1.09	2.20	5.16	4871	7.1	
✓ 1390		.35	.69	.98	494	6.9	
✓ 1391		.59	1.60	1.94	498.5	4.5	
✓ 1392		.83	2.23	3.24	498.8	1.3	
✓ 1393		.59	1.30	.85	504.9	5.1	
✓ 1394		.65	1.94	2.00	510.5	5.6	
✓ 1395		.74	1.63	2.94	517.1	6.6	
✓ 1396		1.03	2.13	4.38	521.4-5293	7.9	
✓ 1397		.03	.19	1.02	5370	7.7	
✓ 1398		.15	.95	2.40	538.9	8.9	
✓ 1399		.06	.07	.18	538.9-525.9	2.9	
✓ 1400		1.18	2.85	7.32	552	6.1	7.20 7.03 149
✓ 527		1.71	3.45	6.84	561	9.0	15.1
✓ 528		.44	1.10	1.00	580-581.6	1.6	
✓ 529		1.56	3.53	6.12	589.0	7.4	
✓ 530		1.32	2.48	6.00	593.7	4.7	
✓ 531		1.94	4.05	6.48	599.4	5.7	3.14 5.80 1.50
✓ 532		1.24	2.50	4.86	606.8	7.4	15.2
✓ 533		1.47	3.00	2.82	612.3	5.5	
✓ 534		1.12	2.85	2.88	617.9	5.6	
✓ 535		1.50	3.15	4.92	626.0	8.1	3.45 4.92 1.50
✓ 536		.59	1.43	3.48	632.5	6.5	8.1
✓ 537		.44	1.13	1.98	638.8	6.3	
✓ 538		1.50	3.00	4.26	644.5	2.7	
✓ 539		1.09	2.35	4.74	646.7	5.2	2.77 4.21 1.21
✓ 540		1.44	3.15	5.04	649.5	2.8	17.8
✓ 541		1.12	2.85	3.48	656.6	7.1	
✓ 542		.88	1.74	1.39	662.8	5.4	
✓ 543		.59	1.63	.84	664.8	2.8	
✓ 544		2.50	5.93	8.40	7014-7110	9.6	547 9.21 2.43
✓ 545		2.35	4.88	10.31	-718.2	7.2	16.8
✓ 546		.12	.23	1.38	7210	2.8	
✓ 547		3.09	6.08	9.96	726.5	5.5	
✓ 548		3.74	8.10	14.88	732.5	6.0	7.15 12.2 3.27
✓ 549		3.00	7.20	11.78	738.3	5.8	17.3
✓ 550		.88	2.00	2.46	740.3	2.8	
✓ 551		.12	.33	.85	746.0	5.7	
✓ 552		.44	1.10	1.48	756.5	10.5	
✓ 553		1.68	3.75	7.68	8339-840.1	6.2	3.25 2.52 1.8
✓ 554		.15	.20	.55	-843.5	3.4	6.2
✓ 555		1.56	4.20	2.70	848.4	2.9	
✓ 556		.21	.35	.66	855.0	6.6	
✓ 557		.59	1.18	2.52	866.0	11.8	
✓ 558		.24	.25	.60	870.5	4.5	
✓ 559		.59	1.55	3.30	916.8-922.8	6.0	
✓ 560		.21	.83	1.90			

586, 10.05, 2.65
36.9

ASSAYER. K. Hoyland for H. Spalding

SEPTEMBER 7, 1974.

ASSAY CERTIFICATE

WHITEHORSE ASSAY OFFICE LTD.
BOX 4518 WHITEHORSE Y.T.

PHONE 667 2694

NO. 8612-55

SAMPLE RECEIVED FROM

KERR ADDISON MINES

SAMPLE NO.	GOLD Oz. Per Ton	SILVER Oz. Per Ton	LEAD	ZINC				
<i>A-30</i>								
✓ 561		.15	.09	.57	9228-9271	4.3		
✓ 562		1.82	5.10	12.43	-9285	1.4		
✓ 563		.74	1.88	1.86	988-993	5.0		
✓ 564		2.09	4.43	6.24	11162-11187	2.0		
✓ 565		.18	.33	.37	-1123	4.8		
✓ 566		1.91	4.73	5.76	1124	1.0		

ASSAYER. *K. Hoyland for B. Spalding*

RECEIVED

ASSAY CERTIFICATE

DATE. SEPTEMBER 23, 1974.

SEP 25 1974

WHITEHORSE ASSAY OFFICE LTD.

FILE NO. 8672-30

KERR ADDISON MINES LTD.

BOX 4518 WHITEHORSE Y.T.

PHONE 667 2694

PER KERR ADDISON MINES

SAMPLE RECEIVED FROM

KERR ADDISON MINES

SAMPLE NO.	GOLD Oz. Per Ton	SILVER Oz. Per Ton	LEAD	ZINC			
A-31 567		2.00	4.95	7.05	376.1-380.5	4.4	4.95, 7.05, 2.00
568		.74	1.33	1.18	429.2-432.2	4.0	
569		.59	1.68	1.62	438.5-441.0	2.5	4.21
570		.59	1.15	1.35	-446.1	5.1	
571		.18	.32	.24	486.8-488.2	1.4	4.08, 3.96, 1.46
572		1.76	4.58	1.86	553.0-557.0	6.0	
573		1.29	3.90	3.60	-561.0	5.0	14.2
574		1.15	3.38	2.76	-567.0	3.0	
575		.44	.64	.34	571.0	2.0	
A29 601	3.1 27.4	.29	.93	2.22	1209-1218	9.0	
602		.53	1.23	2.22	1228	10.0	
603 ✓		.21	.65	1.28	12314	3.4	
76.1 604		.41	1.65	2.58	1239	7.6	
3.09 4.51 605	2.5170 15.1	.29	.80	1.42	1244	5.0	
606		.44	1.18	1.46	1254	10.0	
607		.71	1.44	2.40	1265.6-1275	9.4	
608		.47	1.23	2.00	1285	10.0	
25.1 609		.50	2.00	4.02	1292.5	7.5	
610 ✓		.65	1.28	2.94	1324.3-1329	4.7	
611 ✓		1.09	1.20	4.20	1334-1338.5	4.5	
612		1.29	2.28	4.92	-1340.0	1.5	2.22, 3.84, 1.02
26.0 613 ✓		1.24	2.50	4.60	1345	5.0	
614 ✓		.94	1.93	4.20	1350	5.0	26.0
615		.88	2.48	1.36	1356	6.0	
616 ✓		.88	2.33	5.10	1360	4.0	
617 ✓		.15	.22	.41	1430.6-1433.2	2.6	
618 ✓		2.35	3.68	16.67	1433.2-1439	5.8	2.71, 11.6, 1.65
9.8 619		.62	1.35	5.40	-1440.5	1.5	
620		.65	1.30	3.84	1443	2.5	9.8
621		.35	.58	1.60	1450-1453.2	3.2	

ASSAYER. *L. Anderson for H. Spalding*

RECEIVED

ASSAY CERTIFICATE

DATE. SEPTEMBER 26, 1974

SEP 30 1974

WHITEHORSE ASSAY OFFICE LTD.
BOX 4518 WHITEHORSE Y.T.

FILE NO. 8701-16

KERR ADDISON MINES LTD.

PHONE 667 2694

PER _____
KERR ADDISON MINES

SAMPLE RECEIVED FROM

SAMPLE NO.	GOLD Oz. Per Ton	SILVER Oz. Per Ton	LEAD	ZINC			
<i>A-32</i>							
622		.06	.09	.11	5085-5130	45'	16 21 16
623		.41	1.05	2.46	-5185	55'	
624		1.24	3.23	3.30	5785-5813	2.8'	3.15, 5.15, 1.75
625		.74	1.80	3.03	746.8-800.5	3.7'	6.0
626		3.38	5.33	8.61	800.5-802.8	2.3'	
627		.77	1.65	2.82	931.3-936.3	5.0'	2.99 3.87 1.33
628		2.06	4.73	5.22	936.3-940.2	3.9'	8.9'
629		.59	.95	.95	940.2-949	8.8'	
630		.38	.80	1.11	949-959	10.0'	
631		.59	1.14	1.08	-969	10.0'	
632		.41	.68	.60	-979	10.0'	
633		.50	.88	1.24	989	10.0'	
634		.65	1.38	1.64	-994	5.0'	
635		.15	.10	.36	1004	10'	
636		.15	.14	.24	1014	10'	
637		.18	.10	.26	1024	10'	
↓							

ASSAYER. *K. Haydon for J. Spalding*

RECEIVED

ASSAY CERTIFICATE

DATE. OCTOBER 2, 1974.

OCT 4 - 1974

WHITEHORSE ASSAY OFFICE LTD.
BOX 4518 WHITEHORSE Y.T.

FILE NO. 8723-26

KERR ADDISON MINES LTD.

PHONE 667 2694

PER _____

SAMPLE RECEIVED FROM _____

KERR ADDISON MINES

SAMPLE NO.	GOLD Oz. Per Ton	SILVER Oz. Per Ton	LEAD	ZINC			
<i>A33</i> 576		.50	1.08	1.56	340.2-345.5	5.3	
577		.29	.35	.50	-349	3.5	
578		.15	.20	.11	351.6	2.6	
579		.29	.49	.50	353.0	1.4	
<i>A32</i> 638		.15	.12	.42	1024-1034	10	
639		.29	.14	.50	-1044	10	
640		.18	.13	.30	1054	10	
641		.15	.13	.44	-1064	10	
642		.09	.10	.23	1068	4.5	
643		.59	1.43	1.60	1070.3	2.3	
644		.47	.94	1.48	1073.1	2.8	
645		.65	1.24	1.04	1075-1076.4	1.4	
✓ 646		1.03	1.93	1.56	-1078.7	2.3	
↑ 647		.44	.77	.52	1080.0	1.3	
<i>A35</i> 648		.15	.09	.07	520-521	1.0	
649		2.41	< 6.00	3.72	521-524	3.0	3.57, 2.23 15.5
✓ 650		1.27	< 1.60	.37	-530	6.0	
✓ 651		1.91	< 4.28	3.72	536.5	6.5	4.33, 4.28, 1.79
652		.44	< .39	.04	539.9	7.234	
✓ 653		2.79	< 7.35	7.75	544-543.9	4.0	22.7
654		1.09	< 1.60	1.64	545.9	2.0	
✓ 655		1.47	< 3.53	3.66	546-547.0	8.16	
656		.65	< 1.60	1.64	556.3	2.3	
✓ 657		2.21	< 5.33	4.68	562.6	6.3	
658		.29	.45	.62	566	3.4	
✓ 659		.44	.83	.72	937-947	10.0	

ASSAYER. K. Heyland for H. Spalding

RECEIVED

ASSAY CERTIFICATE

DATE. OCTOBER 2, 1974

OCT 7 - 1974

WHITEHORSE ASSAY OFFICE LTD.

FILE NO. 6733-13

KERR ADDISON MINES LTD.

BOX 4518 WHITEHORSE Y.T.

PHONE 667 2694

SAMPLE RECEIVED FROM PER KERR ADDISON MINES

SAMPLE NO.	GOLD Oz. Per Ton	SILVER Oz. Per Ton	LEAD	ZINC			
A35-J660		.53	1.25	.86	907-952	5.0	
• J661		.15	.13	.06	1068-1-10734	5.3	
• J662		.68	1.10	1.18	1076-1078	2.0	
• J663		.03	.20	.11	10815-10838	2.3	
• J664		.56	1.23	1.02	10838-10882	4.4	
• J665		.29	.53	.56	-1098	9.8	
• J666		.26	.75	.63	-11075	9.5	
• J667		.77	2.10	2.58	1113.5	6.0	
• 668		.59	1.35	2.00	1119.7	6.2	
• J669		.32	.68	.59	1126.6-11282	1.6	
• J670		1.32	3.83	4.44	11282-11380	9.8	3.83, 4.44, 1.32
• J671		.29	.50	.62	-1141	3.0	9.8'
• J672		.44	1.25	1.74	-1145	4.0	

ASSAYER. K. Heyland for H. Spalding

DATE. OCTOBER 6, 1974.

ASSAY CERTIFICATE

FILE NO. 8739-38

WHITEHORSE ASSAY OFFICE LTD.
BOX 4518 WHITEHORSE Y.T.

PHONE 667 2694

SAMPLE RECEIVED FROM

KERR ADDISON MINES

SAMPLE NO.	GOLD Oz. Per Ton	SILVER Oz. Per Ton	LEAD	ZINC				
A-35								
673		.18	.27	.52	1145-1155	10.0		
✓674		.15	.15	.58	-1165	11.0		
675		1.35	3.75	3.90	11715	3.7		
✓676		.12	.20	.37	11780	3.5		
✓677		.12	.17	.44	11850	3.0		
✓678		.65	1.80	1.60	11880-11900			
✓679		.59	1.75	1.42				
A 37 ✓680		.47	.97	1.12	2141-2241	10'		
681	210'	.44	.77	.74	-231	7		
682		.29	.35	.72	.235	4'		
683 ✓	210'	1.76	4.58	5.40	237.5	2.5		
684	210'	.53	.68	.70	243	5.5		
685		2.15	7.35	6.12	248	5.0		
686		.88	2.23	3.60	250.5	2.5		
687 ✓	10' / 10.5'	1.88	2.63	1.96	253.5	3.0		
688 ✓	10' / 10.5'	1.85	7.20	9.44	260.0	6.5		
689	10' / 10.5'	.65	2.03	2.82	263	3.0		
690 ✓	10' / 10.5'	2.79	8.41	12.75	271	8.0		
691 ✓	10' / 10.5'	1.68	5.55	7.32	276	5.0	3.62, 5.21, 1.23	
692	10' / 10.5'	.50	1.04	1.16	280.7	4.7	109.0	
693 ✓	10' / 10.5'	2.97	9.39	14.20	283.3	2.6	(235 - 344)	
694 ✓	10' / 10.5'	1.03	2.78	5.46	293	9.7	293 - 297	
695	10' / 10.5'	1.03	2.50	5.16	293	5.3		
696 ✓	10' / 10.5'	1.41	4.05	5.88	313	10.0		
697	10' / 10.5'	1.09	2.50	4.14	323	10.0		
698 ✓	10' / 10.5'	.47	1.12	2.28	333	10.0		
699	10' / 10.5'	.74	2.15	3.12	338.2	5.2		
700	10' / 10.5'	1.47	4.13	6.00	341.0	5.8		
701	344.0 - 358.6	.18	.50	.96	350	6.0		
702	344.0 - 358.6	.44	1.23	1.34	350	6.6		
703	344.0 - 358.6	.18	.39	.58	368.6	1.8		
704	344.0 - 358.6	1.56	3.83	4.68	370.4 - 375.6	5.2	3.83, 4.68, 1.56	
705	344.0 - 358.6	.24	.29	.36	386	10.4	5.2	
706 ✓	344.0 - 358.6	.15	.07	.20	396	10.0		
707 ✓	344.0 - 358.6	.29	.40	.60	402.2	6.2		
708	344.0 - 358.6	.80	2.08	2.88	406.1	3.9		
709 ✓	344.0 - 358.6	.59	1.60	1.72	409.8	3.7		
710 ✓	344.0 - 358.6	1.12	3.23	6.60	414.0	4.2	3.23, 6.60, 1.12	

ASSAYER. K. Hayward for H. Spalding

DATE. OCTOBER 6, 1974.

FILE NO. 8739-38

ASSAY CERTIFICATE

WHITEHORSE ASSAY OFFICE LTD.
BOX 4518 WHITEHORSE Y.T.

PHONE 667 2694

SAMPLE RECEIVED FROM

KERR ADDISON MINES

SAMPLE NO.	GOLD Oz. Per Ton	SILVER Oz. Per Ton	LEAD	ZINC				
A-35								
673		.18	.27	.52	1145-1155	10.0		
674		.15	.15	.58	-1165	12.0		
675		1.35	3.75	3.90	11715	2.7		
676		.12	.20	.37	11750	3.5		
677		.12	.17	.44	11850	10.0		
678		.65	1.80	1.60	11918-1208	5.2		
679		.59	1.75	1.42				
A37 680		.47	.97	1.12	214-224	10		
681		.44	.77	.74	-231	7		
682		.29	.35	.72	-235	4		
683		1.76	4.58	5.40	237.5	2.5		
684		.53	.68	.70	243	5.5		
685		2.15	7.35	6.12	248	5.0		
686		.88	2.23	3.60	250.5	2.5		
687		.88	2.63	1.96	253.5	3.0		
688		1.85	7.20	9.44	260.0	6.5		
689		.65	2.03	2.82	263	5.0		
690		2.79	8.41	12.75	271	8.0		
691		1.68	5.55	7.32	276	5.0	3.62, 5.21, 1.23	
692		.50	1.04	1.16	280.7	4.7	109.0	
693		2.97	9.39	14.20	283.3	2.6		
694		1.03	2.78	5.46	293	9.7		
695		1.03	2.50	5.16	303	5.3		
696		1.41	4.05	5.88	313	10.0		
697		1.09	2.50	4.14	323	10.0		
698		.47	1.12	2.28	333	10.0		
699		.74	2.15	3.12	338.2	5.2		
700		1.47	4.13	6.00	344.0	5.8		
701		.18	.50	.96	350	6.0		
702		.44	1.23	1.34	350	3.66	6.6	
703		.18	.39	.58	355.6	370.4	1.8	
704		1.56	3.83	4.68	370.4-375.6	5.2	3.83, 4.68, 1.56	
705		.24	.29	.36	386	10.4	5.2	
706		.15	.07	.20	396	10.0		
707		.29	.40	.60	402.2	6.2		
708		.80	2.08	2.88	406.1	3.9		
709		.59	1.60	1.72	409.8	3.7		
710		1.12	3.23	6.60	414.0	4.2	3.23, 6.60, 1.12	
							4.2	

ASSAYER. *K. Hayward for M. Spalding*

ASSAY CERTIFICATE

WHITEHORSE ASSAY OFFICE LTD.
BOX 4518 WHITEHORSE Y.T.

PHONE 667 2694

DATE. OCTOBER 7, 1974.

FILE NO. 8741-25

SAMPLE RECEIVED FROM .

KERR ADDISON MINES

SAMPLE NO.	GOLD Oz. Per Ton	SILVER Oz. Per Ton	LEAD	ZINC			
A38-711		.85	1.80	1.40	6056-608	2.4	
712		1.24	2.50	3.00	-616.5	8.5	
713		.44	1.03	.98	-621	4.5	
714		1.18	3.23	2.40	630.3	9.3	
715		.29	.90	1.00	6317-640.5	8.8	6.08, 4.86, 2.27
716		2.27	6.08	4.86	705.5-710	4.5	4.5
717		2.53	8.25	8.55	740-748	8.0	6.90, 8.07, 1.74
718		2.06	5.63	7.61	-758.5	8.5	16.5
719		.38	1.18	1.56	898-900.4	2.4	
720		2.79	8.55	5.16	903.6	3.2	6.97, 3.16, 2.27
721		1.62	4.95	ok → .59	check -906.1	2.5	5.7
722		.50	1.58	.60	-912.8	6.7	15.8
723		1.82	4.50	7.40	916.2	3.4	10.1
724		.21	.14	.18	921	4.8	
725		.18	.14	.16	927	6.0	
726		3.09	7.65	9.75	932.4	5.4	
727		.29	.43	.42	942.4	10.2	
728		.56	1.20	.78	951.5	6.5	
729		.44	.80	1.20	957.5	6.0	
730		.32	.63	.58	961	3.5	
731		1.76	5.40	4.86	961-963	2.0	
732		.27	.52	.85	968.3	5.3	2.51, 2.33, 1.03
733		1.71	4.35	4.50	972	3.7	17.4
734		1.06	2.20	1.56	978.4	6.4	
735		.74	2.10	1.94	1119-1122.5	3.3	

ASSAYER.

L. Heyland for H. Spalding

ASSAY CERTIFICATE

WHITEHORSE ASSAY OFFICE LTD.
BOX 4518 WHITEHORSE Y.T.

PHONE 667 2694

DATE. OCTOBER 11, 1974.

FILE NO. 8749-27 & 8755-22

SAMPLE RECEIVED FROM

KERR ADDISON MINES

SAMPLE NO.	GOLD Oz. Per Ton	SILVER Oz Per Ton	LEAD	ZINC				
8749-27: 736 ✓		.21	.34	.18	1122.3-1126.3	4.0		
737 ✓		.88	1.98	1.76	1128.1	2.8		
738 ✓		.32	.58	.45	1137.5	2.2		
739 ✓		.80	2.10	1.98	1137.3-1141.2	6.7		
740 ✓		1.38	3.60	3.00	1141.2-1145.2	9.2		
741 ✓		.15	.60	.58	1145.2-1149.1	7.3		
742 ✓		.88	2.00	2.00	1149.1	3.9		
A39- 743 ✓		.50	1.00	.69	1149.1-1153.0	2.2		
744 ✓		.59	1.40	1.10	1153.0-1156.9	2.5		
745 ✓		.15	.23	.23	1156.9-1160.8	2.4		
746 ✓		.50	1.15	.88	1160.8-1164.7	2.5		
747 ✓		.44	.93	1.44	344.5-351.8	7.3		
748 ✓		.59	2.35	2.40	-351.8	1.1		
749 ✓		.35	.14	.23	-361.3	5.1		
750 ✓		1.03	2.93	2.22	-371.8	4.7		
751 ✓		.74	1.65	1.16	371.7	5.7	1.63	1.57
752 ✓		.94	2.38	2.76	371.7	2.0	44.8'	0.63
753 ✓		.18	.33	.29	371.7	2.5		
754 ✓		.29	.84	1.04	-381.3	2.3		
A-41 755 ✓	116.0-727	.80	1.60	2.28	715-719.7	4.7		
756 ✓		.24	.13	.11	-727	2.3		
757 ✓		1.50	2.45	1.50	727.0	3.5	6.72	6.40
7.5.0-751.6 758 ✓	730.5-741.0	3.38	6.45	7.07	734	3.5	14'	2.98
759 ✓		3.53	9.00	8.53	741	7.0		
760 ✓	741-751.6	.35	.38	.27	749	8.0		
761 ✓		.77	1.50	.49	754	5.0		
762 ✓	751.6-761.6	.06	.15	.17	759	5.0		
8755-22: 763 ✓		2.65	6.15	7.20	766	3.6		
764 ✓		.29	.63	.28	766.6	5.0		
765 ✓		.29	.50	.34	773	2.4		
766 ✓		.44	1.15	.80	774.A-783.5	2.1		
767 ✓		.21	.33	.24	787	2.5		
768 ✓		.24	.58	.36	791-798	7.07		
769 ✓		.32	.35	.20	800.7-804.4	3.7		
770 ✓		.03	.01	.01	806.8	2.4		
771 ✓	846.8-856.8	.29	.35	.26	830.6	3.8		
772 ✓	10	2.12	5.48	6.48	836	5.5		
773 ✓		.18	.18	.23	860.6	5.0		
774 ✓		.29	.35	.44	865.5	4.9		
775 ✓	856.8-875	1.03	2.20	1.80	873.2	7.7		
776 ✓	18.2	.21	.28	.31	875.2	1.8		
777 ✓		.59	1.18	1.24	915.5-922.5	7.0		
778 ✓	921.5-931.5	1.71	4.13	4.38	922.5-928.5	1.0	10.0	
779 ✓	10	.77	1.50	1.64	-931.5	5.0		
780 ✓		.35	.55	.23	-936.5	5.0		
781 ✓	931.5-949.8	.03	.09	.08	-937.2	2.8		
782 ✓		.29	.45	.30	944.5	5.2		
783 ✓		.03	.04	.07	947.4	2.9		
784 ✓	18.3	.47	1.23	1.20	949.8	2.4		

ASSAYER. *L. Hayward for M. Goulding*

ASSAY CERTIFICATE

WHITEHORSE ASSAY OFFICE LTD.
BOX 4518 WHITEHORSE Y.T.

PHONE 667 2694

DATE. OCTOBER 19, 1974.

FILE NO. 8763-15

SAMPLE RECEIVED FROM

ADX MINERALS CORPORATION

SAMPLE NO.	GOLD Oz. Per Ton	SILVER Oz. Per Ton	LEAD	ZINC			
<i>224</i>		.03	.17	.16	253-260	5'	
224		.15	.33	.16	260-266	6.5'	
225		.10	.72	.20	50.5-57.5	7.0	
<i>226</i>		.03	.22	.06	-63.5	6.0	
227		.38	.48	.36	68.0	4.5'	
<i>228</i>		2.06	4.80	5.88	68-75	7.0	448, 412, 168
229		1.27	4.13	2.22	-81.5	6.5'	13.5'
230		.06	.05	.04	-85.0	3.5'	
231		.59	1.05	1.60	111-116.0	5.0	
232		.15	.14	.07	-125.0	9.0	
233		.80	1.28	.60	-135.0	10.0	
234		.18	.18	.03	-141.5	6.5'	
235		.03	.05	.02	-145.0	3.5'	
236		.12	.07	.12	163-167.0	4.0	
237		.59	1.38	2.82	163-167.7	4.7	
238							

ASSAYER.

F. H. ...

DATE. OCTOBER 21, 1974.

FILE NO. 8765-44

*Rec'd 3 copies separately,
this time copy? good*

ASSAY CERTIFICATE

WHITEHORSE ASSAY OFFICE LTD.
BOX 4518 WHITEHORSE Y.T.

PHONE 667 2694

SAMPLE RECEIVED FROM

KERR ADDISON MINES

SAMPLE NO.	GOLD Oz. Per Ton	SILVER Oz. Per Ton	LEAD	ZINC			
785✓		.53	1.25	.99			
786✓		1.18	3.00	3.60			
787✓		2.59	7.20	10.0			
788✓		1.18	3.45	4.32			
789✓		.74	1.98	1.71			
790✓		.59	1.58	1.47			
791✓		.74	1.80	1.34			
792✓		.59	1.40	1.44			
A42 793✓		1.03	3.15	3.66			
794✓		2.35	5.93	7.44	146-167	21	
A45 795✓		.29	.73	3.18	170	3	7'
796✓		.83	2.33	5.28	174	4	
797✓		.91	2.33	7.20	183.5	7.5	16'
798✓		1.44	3.90	5.22	190	6.5	
799✓		1.76	4.43	12.1	200	10.	16'
800✓		1.59	4.50	5.40	206	6	
801✓		2.35	6.00	9.6	210.5-218	7.5	10'
802✓		.56	2.30	4.42	220.5	2.5	
803✓		.29	.42	.98	240-250	10	
804✓		3.03	6.90	14.2	255	5	
805✓		2.94	8.25	16.2	260	5	
806✓		3.53	8.63	16.8	266	6	27'
807✓		3.82	8.74	17.0	275	9	
808✓		2.94	7.50	15.6	277	2	
809✓		.29	1.25	2.00	284	7	
810✓		1.65	3.60	6.60	288.5	4.5	
811✓		.15	.08	1.12	545-550.5	5.5	11'
812✓		.15	.19	.59	556	5.5	
813✓		1.09	3.23	5.28	562	6	10'
814✓		.24	.70	2.28	566	4	
815✓		.56	1.48	.86	583-586	3.5	
816✓		1.00	1.88	3.84	624-636	12	
817✓		2.79	6.23	8.82	640	4	
818✓		1.12	1.80	4.80	645	5	11'
819✓		2.85	4.95	8.28	647	2	
820✓		.88	1.98	1.98	652.6-660	7.4	
821✓		.44	1.04	.63	665	5	10'
822✓		1.76	6.53	3.66	670	5	
823✓		.44	.97	.46	680	10	20'
824✓		.26	.27	.37	685	5	
825✓		.44	.94	1.30	690	5	
826✓		.88	2.20	1.55	692	2	
827✓		.94	2.20	3.24	697	5	9.5
828		.88	1.63	3.12	699.5	2.5	



ASSAYER.

K. H. ...

DATE. OCTOBER 21, 1974.

ASSAY CERTIFICATE

FILE NO. 8765-44

WHITEHORSE ASSAY OFFICE LTD.
BOX 4518 WHITEHORSE Y.T.

PHONE 667 2694

SAMPLE RECEIVED FROM

KERR ADDISON MINES

SAMPLE NO.	GOLD Oz. Per Ton	SILVER Oz. Per Ton	LEAD	ZINC			
785 ✓		.53	1.25	.99	367.7	378	10.3
786 ✓		1.18	3.00	3.60	378	385	7.0
787 ✓		2.59	7.20	10.0		387	2.0
788 ✓		1.18	3.45	4.32		388.2	1.2
789 ✓		.74	1.98	1.71	388.2	395	6.8
790 ✓		.59	1.58	1.47		400	5.0
791 ✓		.74	1.80	1.34		405	5.0
792 ✓		.59	1.40	1.44		409.3	4.3
793 A42		1.03	3.15	3.66		413.2	2.3
794 A45		2.35	5.93	7.44	146	167	21.0
795		.29	.73	3.18		170	3'
796		.83	2.33	5.28		174	4'
797		.91	2.33	7.20		183.5	9.5
798		1.44	3.90	5.22		190	6.5
799		1.76	4.43	12.1		200	10.0
800		1.59	4.50	5.40		206	6.0
801		2.35	6.00	9.6	210.5	218	7.5
802		.56	2.30	4.42	218	220.5	2.5
803		.29	.42	.98	240	250.0	10.0
804		3.03	6.90	14.2	250	255	5'
805		2.94	8.25	16.2		260	5'
806		3.53	8.63	16.8		266	6'
807		3.82	8.74	17.0		275	9'
808		2.94	7.50	15.6		277	2'
809		.29	1.25	2.00		284	7'
810		1.65	3.60	6.60		288.5	4.5
811		.15	.08	1.12	545	550.5	5.5
812		.15	.19	.59		556	5.5
813		1.09	3.23	5.28		562	6.0
814		.24	.70	2.28		566	4.0
815		.56	1.48	.86	583	586.5	3.5
816		1.00	1.88	3.84	624	636.0	12.0
817		2.79	6.23	8.82		640	4.0
818		1.12	1.80	4.80		645	5.0
819		2.85	4.95	8.28		647	2.0
820		.88	1.98	1.98	652.6	660	7.0
821		.44	1.04	.63		665	5.0
822		1.76	6.53	3.66		670	5.0
823		.44	.97	.46		680	10'
824		.26	.27	.37		685	5'
825		.44	.94	1.30		690	5'
826		.88	2.20	1.55		692	2'
827		.94	2.20	3.24		697	5'
828		.88	1.63	3.12		698	2.5

3.87, 4.94, 1.45
10.2

4.24, 7.38, 1.49
60.0

Note: 220.5
250
NET GRS

5.07, 8.30, 1.90

10.0

6.39, 12.48, 2.61
38.5

2.88, 5.30, 1.49
23.0

6.53, 36.6, 1.76
5.0

ASSAYER. *K. Hayward for H. Smith*

RECEIVED ASSAY CERTIFICATE

DATE. OCTOBER 24, 1974.

OCT 28 1974
WHITEHORSE ASSAY OFFICE LTD.
BOX 4518 WHITEHORSE N.T.

FILE NO. 8761-15- & 8763-15 & 8755-8

PHONE 667 2694

SAMPLE RECEIVED FROM

AEX MINERALS CORPORATION (KERR ADDISON MINES)

SAMPLE NO.	GOLD Oz. Per Ton	SILVER Oz. Per Ton	LEAD	ZINC			
<u>8761-15:</u>							
<i>A-40</i> <i>(Aex)</i> ✓209		.15	.43	.58			
✓210		.06	.04	.20			
✓211		.03	.10	.36			
✓212		.09	.28	.80			
✓213		.12	.08	.67			
✓214		.12	.35	.36			
✓215		.44	.42	.88			
✓216		.15	.08	.21			
<i>A44</i> <i>AEX</i> ✓217		.15	.28	.49	120-130	10'	} 54' <i>A44 Pb Zn</i>
✓218		.09	.09	.20	-140	10'	
✓219		.09	.13	.26	-150	10'	
✓220		.12	.25	.22	-160	10'	
✓221		.06	.15	.17	-167	7'	
✓222		.09	.10	.33	174	7'	
✓223		.09	.10	.25	295-255	10'	
✓224		.03	.17	.16	-260	5'	
✓225		.15	.33	.16	266.5	6.5'	
✓226		.03	.17	.16			
<u>8763-15:</u>							
<i>A47</i> <i>AEX</i> ✓227		.18	.72	.20			} 448, 412, 1.68 135'
✓228		.03	.22	.06			
✓229		.38	.48	.36			
✓230		2.06	4.80	5.88			
✓231		1.27	4.13	2.22			
✓232		.06	.05	.04			
✓233		.59	1.05	1.60			
✓234		.15	.14	.07			
✓235		.80	1.28	.60			
✓236		.18	.18	.03			
✓237		.03	.05	.02			
✓238		.12	.07	.12			
✓239		.59	1.38	2.82			
<u>8755-8:</u>							
<i>A-36</i> <i>AEX</i> ✓201		TR	.05	.86			
✓202		TR	.24	3.12			
✓203		TR	.08	.47			
✓204		.15	1.13	1.44			
✓205		.47	.67	.94			
✓206		.97	3.00	1.34			
✓207		.15	.25	.50			
✓208		.44	.83	1.38			

ASSAYER. *A. Hayward for B. Spalding*

DATE. OCTOBER 28, 1974.

FILE NO. 8776-19

ASSAY CERTIFICATE

WHITEHORSE ASSAY OFFICE LTD.
BOX 4518 WHITEHORSE Y.T.

PHONE 667 2694

SAMPLE RECEIVED FROM

KERR ADDISON MINES

SAMPLE NO.	GOLD Oz. Per Ton	SILVER Oz. Per Ton	LEAD	ZINC				
<u>A-51</u>								
-844 ✓		.44	.75	1.70	690.2-700	9.8		
-845 ✓		1.59	4.28	4.26	-702	2.0		
-846 ✓		.38	.90	1.34	976-983	7.0		
-847 ✓		1.12	2.38	2.88	-987.9	4.9		
-848 ✓		.35	.80	.62	988.5-997.7	9.2		
-849 ✓		.12	.18	.18	-1010	12.3		
-880 ✓		.44	1.23	.90	1020.8-1011.5	1.5		
-881 ✓		.15	.18	.27	-1021.5	10.8		
-882 ✓		.35	.83	.70	-1029.7	8.2		
-883 ✓		.62	2.05	1.76	1065.6-1088.5	5.7		
-884 ✓		1.03	2.35	2.28	1100.2-1103.2	3.0		
-885 ✓		.88	1.95	1.62	1107.6-1111.1	3.5		
-886 ✓		.06	.03	.16	-1115.0	4.9		
-887 ✓		.80	1.90	1.84	1116-1120	1.0		
-888 ✓		.15	.20	.27	-1126.0	6.0		
-889 ✓		.32	.83	.82	-1129.2	3.2		
-890 ✓		.35	.69	.86	-1133.0	3.8		
-891 ✓		1.41	4.28	6.12	1135.3	2.3		
-892 ✓		.59	1.33	1.60	1139.5	4.2		

ASSAYER. *K. Hayward for H. Spalding*

RECEIVED

ASSAY CERTIFICATE

DATE. OCTOBER 30, 1974.

NOV - 1 1974

FILE NO. 8778- 21

KERR ADDISON MINES LTD.

WHITEHORSE ASSAY OFFICE LTD.
BOX 4518 WHITEHORSE Y.T.

PHONE 667 2694

PER

SAMPLE RECEIVED FROM

KERR ADDISON MINES

SAMPLE NO.	GOLD Oz. Per Ton	SILVER Oz. Per Ton	LEAD	ZINC				
<i>A52</i> 861 ✓		5.00	11.0	20.45	256-257			Pb Zn Ag
862 ✓		.80	1.75	2.22	279-281.8	2.8'	6.01	7.85 2.39
863 ✓		3.21	8.18	10.72	282.5-288	5.5'		8.2 9.0'
864 ✓		.21	.25	.55				
865 ✓		.21	.18	.44				
866 ✓		1.47	3.90	5.46	517-520.5	3.5'	} 10.5'	3.45 5.5 1.21
867 ✓		1.32	3.23	5.52	-527.5	7.0'		10.5'
868 ✓		1.47	4.65	4.20	575.5-579	3.5'	} 28.5'	
869 ✓		1.21	2.50	3.84	-589	10.0'		
870 ✓		1.56	3.83	4.98	-596	7.0'		3.60 4.61 1.45
871 ✓		1.21	2.45	3.36	-600.5	4.5'		28.5'
872 ✓		2.27	6.75	8.16	604	3.5'		
873 ✓		.59	1.23	1.94				
874 ✓		.29	.60	.99				
875 ✓		.38	1.28	1.10				
876 ✓		.21	.27	.40				
877 ✓		.24	.45	.56				
878 ✓		.12	.32	.40				
879 ✓		.15	.48	.16				
893		.21	.27	.37				
894		.06	.05	.15				

ASSAYER. *K. Heyland for H. Spaulding*

DATE. NOVEMBER 6, 1974.

FILE NO. 8788-26

ASSAY CERTIFICATE

WHITEHORSE ASSAY OFFICE LTD.
BOX 4518 WHITEHORSE Y.T.

PHONE 667 2694

SAMPLE RECEIVED FROM

KERR ADDISON MINES

SAMPLE NO.	GOLD Oz. Per Ton	SILVER Oz. Per Ton	LEAD	ZINC			
<i>A53</i>							
- 580 ✓		.44	1.13	2.88	492.498	6.0	
- 581 ✓		.88	2.25	4.20	-502	4.0	} 10'
- 582 ✓		.80	2.00	4.02	-508	6.0	
- 583 ✓		.53	1.50	2.70	-515	3.5	} 20'
- 584 ✓		1.21	3.90	3.78	-518	6.5	
- 585 ✓		.38	.70	1.04	-524.7	6.7	
- 586 ✓		.65	1.68	4.02	-529.6	4.9	
- 587 ✓		.21	.52	1.20	547.3 - 554.5	7.2	
- 588 ✓		.29	.57	1.56	562.2 - 567.5	5.3	
- 589 ✓		.26	.38	.78	769.0 - 777.7	8.7	
- 590 ✓		1.53	3.68	6.96	777.7 - 781.8	4.1	} 10'
- 591 ✓		.56	.74	.68	-787.9	6.1	
- 592 ✓		1.82	4.43	6.00	787.9 - 798.0	10.1	} 18.1'
- 593 ✓		2.76	5.40	11.10	-802	4.0	
- 594 ✓		1.03	2.00	3.96	806	4.0	
- 595 ✓		1.03	2.28	1.80	-814.6	8.6	
- 596 ✓		.80	1.55	1.34	-824.6	10.0	
- 597 ✓		1.97	4.73	7.20	824.6 - 828	4.4	} 29.4
- 598 ✓		2.41	5.03	9.59	-836.2	8.2	
- 599 ✓ + 600 + 901		1.91	4.95	8.09	25 samples - 844.0 - 853.0	7.8	
<i>A53</i> - 895 ✓		3.30	7.05	13.81	4615 - 4650	3.5	} 30.5
- 896 ✓		2.94	6.23	13.55	-476	11.0 (100.0)	
- 897 ✓		1.62	3.90	8.53	-478	2.0	
- 898 ✓		1.44	3.08	7.42	-483	5.0	
- 899 ✓		2.94	6.90	17.2	-488	5.0	
- 900 ✓		5.68	10.57	18.79	-492	10.0 (100.15)	
					wt. Average for Section 461.5 - 518'		
					= 4.52 8.93 1.98		
					56.5'		

RECEIVED

NOV 12 1974

KERR ADDISON MINES LTD.

FOR

ASSAYER. *K. Hayward for H. Spalding*

DATE. NOVEMBER 7, 1974.

FILE NO. 8793-22

ASSAY CERTIFICATE

WHITEHORSE ASSAY OFFICE LTD.
BOX 4518 WHITEHORSE Y.T.

PHONE 667 2694

SAMPLE RECEIVED FROM

KERR ADDISON MINES

SAMPLE NO.	GOLD Oz. Per Ton	SILVER Oz. Per Ton	LEAD	ZINC			
600✓		1.88	4.58	7.20	844.0-848.2	(4.2')	} continuation of 507-599 section.
<i>A-53</i> 901✓		2.32	5.33	9.88	848.2-853.0	(4.8')	
902✓		.29	.27	.33	-860	7.0	}
903✓		.44	.75	2.34	-864.9	4.9	
904✓		1.91	5.10	9.83	864.9-868.3	3.4'	} 9.8'
905✓		.62	.53	1.38	868.3-874.7	6.4'	
906✓		2.21	5.55	11.50	874.7-882.4	7.7'	} 3.62 6.67 1.48 19.0' 28.8'
907✓		.53	.60	.69	882.4-887.0	4.6'	
908✓		1.91	5.70	8.71	887.0-893.7	6.7'	} 11.7
909✓		.29	.27	.28	893.7-898	A.3	
910✓		.29	.19	.80	909.1	11.1	} 35.7
911✓		.29	.27	1.38	913.1	4.0	
912✓		.15	.07	.98	919. A	6.3	} 11.7
913✓		.15	.08	1.06	925.1	5.7	
914✓		.62	.89	1.98	925.1-931.1	6.0'	} 4.22 4.41 1.33 13.2'
915✓		1.47	4.35	4.56	1087-1093.0	6.0	
916✓		1.21	4.28	4.44	-1099.5	6.0	} 7
917✓		1.24	3.38	3.60	1100.2	1.2	
918✓		1.79	4.73	6.72	1123 1133.0	10.0	} 7
919✓		.24	.44	.58	1123A 1133A	10.0	
920✓		.06	.04	.03	1133-1141	5.0	}
921✓		.09	.07	.05	1141-1145	4.0	

RECEIVED

NOV 12 1974
KERR ADDISON MINES LTD.

PER.....

ASSAYER.

K. Hayward for J. Spadling

DATE. NOVEMBER 14, 1974.

ASSAY CERTIFICATE

FILE NO. 8804-50

WHITEHORSE ASSAY OFFICE LTD.
BOX 4518 WHITEHORSE Y.T.

PHONE 667 2694

SAMPLE RECEIVED FROM

KERR ADDISON MINES

SAMPLE NO.	GOLD Oz. Per Ton	SILVER Oz. Per Ton	LEAD	ZINC				
1001 ✓		1.03	1.64	2.64				
1002 ✓		.41	.85	1.66				
1003 ✓		1.32	3.00	7.44	4965-5315	5.0		
1004 ✓		.26	.90	.94	5475-5489	1.1		
1005 ✓		2.15	6.00	7.82	5489-5545	5.6		
1006 ✓		.15	.30	.62				
1007 ✓		.50	1.08	2.76	5733-5748 (15)			
1008 ✓		.59	1.23	2.88	5723-5763 (45)		2.26	2.86 0.67
1009 ✓		1.50	5.33	5.16	5768-6000	3.2	12.7	
1010 ✓		.74	1.23	1.38	600-605.0 (50)			
1011 ✓		.47	1.15	1.18				
1012 ✓		.50	1.35	1.72				
1013 ✓		.21	.83	.74				
1014 ✓		.65	1.45	1.72				
1015 ✓		.29	.37	.26	6396-6440	4.4		
1016 ✓		2.85	8.40	12.14	516.5-322.0	5.5		
1017 ✓		1.32	4.05	7.44	-329.0	7.0		
1018 ✓		1.00	2.28	4.98	335.2	6.2		
1019 ✓		.24	1.10	4.02	338.0	2.8	3.72	5.79 1.28
1020 ✓		.88	1.93	4.92	341.0	3.0		35.5
1021 ✓		.88	1.98	3.54	346.0	7.0		
1022 ✓		1.29	5.25	1.26	352.0	4.0		
1023 ✓		.65	1.85	1.52	357.0	7.0		
1024 ✓		.03	.05	4.02	362.0	3.0	1.65, 5.39	0.69
1025 ✓		1.03	2.25	6.72	368.0	6.0	1.0	
1026 ✓		.09	.13	.39	374.0	6.0		
1027 ✓		.06	.07	.44	378.0	4.0		
1028 ✓		.88	1.98	3.78	378-388.0	7.0		
1029 ✓	4-6%	.85	1.98	3.72	391.8	3.8		
1030 ✓		.77	1.78	4.08	398.0	6.2		
1031 ✓	6-8%	1.09	2.30	7.08	402.0	4.0		
1032 ✓		.83	1.73	4.20	408.0	6.0		
1033 ✓		1.32	2.65	5.28	414.0	6.0		
1034 ✓	8-10%	1.32	2.93	5.58	424.0	10.0	2.21	4.82 1.15
1035 ✓		.80	1.65	3.84	434.0	10.0		
1036 ✓	6-8%	.97	2.50	5.46	441.0	7.0	9.7	
1037 ✓		.85	1.98	5.28	445.0	4.0		
1038 ✓		.44	1.00	3.72	450.0	5.0		
1039 ✓		1.59	3.23	7.08	455.0	7.0		
1040 ✓	8-10	1.29	3.30	6.00	460.0	6.0		
1041 ✓	6-8%	1.59	3.98	3.30	460.0	6.7		
1042 ✓		1.18	2.40	4.44	475.9-482.0	6.1		
1043 ✓	4-6	.74	1.00	3.18	-488.0	6.0		
1044 ✓		.62	.89	1.02	493.4K	5.4		
1045 ✓		1.53	4.28	2.00	496.2	2.8	2.71	5.25 1.17
1046 ✓		1.88	5.25	7.93	500.0	6.8		49.6
1047 ✓		.41	.90	4.56	508.0	5.0		
1048 ✓		1.50	3.75	7.92	513.0	5.0		
1049 ✓		1.76	3.68	9.05	517.0	4.0		
1050 ✓		1.18	3.08	7.44	520.3	3.3		

DECEIVED

NOV 18 1974

KERR ADDISON MINES LTD.

ASSAYER.

L. Overland for
GEO. STALDING

352
318.1
35.5

227 475 1.04
142.3

DATE. NOVEMBER 21, 1974.

RECEIVED

ASSAY CERTIFICATE

FILE NO. 8809- 14

NOV 25 1974

WHITEHORSE ASSAY OFFICE LTD.
BOX 4518 WHITEHORSE Y.T.

KERR ADDISON MINES LTD.

PHONE 667 2694

SAMPLE RECEIVED FROM ^{PER} KERR ADDISON MINES

SAMPLE NO.	GOLD Oz. Per Ton	SILVER Oz. Per Ton	LEAD	ZINC				
<i>Asb</i>								
1051		2.18	5.33	7.56	5295-5349	5.4		
1052		3.53	6.83	15.65	5450-5478	2.8		
1053		2.94	6.75	11.64	5370-5385	5.5		
1054		.50	1.13	4.56	-5390	2.5	5.15	10.25 2.31
1055		3.24	7.13	12.30	-5254	6.4		36.7
1056		.91	2.35	4.44	-5700	4.6		
1057		2.79	6.30	13.51	-5317	11.7		
1058		2.35	3.68	13.15	590-5950	5.0		
1059		2.06	2.93	8.04	6054-6080	4.8		
1060		.44	1.08	1.80	-6100	2.0		
1061		2.79	6.00	9.37	-6190	9.0	5.50	9.18 2.61
1062		2.27	4.50	8.16	-6280	7.0		34.6
1063		2.74	6.75	9.42	-6360	8.0		
1064		3.06	6.45	10.65	-6400	4.0		

4.32 7.99 1.96
95.0

ASSAYER. *A. Hayward for*
GEO. SPALDING

RECEIVED

ASSAY CERTIFICATE

DATE. NOVEMBER 23, 1974.

NOV 25 1974

WHITEHORSE ASSAY OFFICE LTD.
BOX 4518 WHITEHORSE Y.T.

FILE NO. 8815-12

KERR ADDISON MINES LTD.

PHONE 667 2694

SAMPLE RECEIVED FROM PER KERR ADDISON MINES LTD.

SAMPLE NO.	GOLD Oz. Per Ton	SILVER Oz. Per Ton	LEAD	ZINC			
A-57 1132 ✓		.74	1.80	3.54	902.4-907.0 (4.6')		
1133 ✓		.74	1.80	4.20	-913 (6.0')		
1134 ✓		.71	1.60	4.32	-916 (3')		
1135 ✓		.62	1.45	3.78	-919 (3')		
1136 ✓		.77	1.48	3.12	930.5(11.5')		
1137 ✓		.94	2.10	4.20	937.4(8.9')		
1138 ✓		.32	.85	.76			
1139 ✓		.77	1.70	1.76			
1140 ✓		.15	.30	.34			
1141 ✓		.18	.09	.14			
1142 ✓		1.00	1.83	4.26	950-951.3 (1.5')		
1143 ✓		.24	.25	.32			

ASSAYER *L. Hayland Jr*
GEN. MANAGER

DATE. NOVEMBER 23, 1974.

RECEIVED

ASSAY CERTIFICATE

FILE NO. 8813-40

NOV 25 1974

WHITEHORSE ASSAY OFFICE LTD.
BOX 4518 WHITEHORSE Y.T.

KERR ADDISON MINES LTD.

PHONE 667 2694

SAMPLE RECEIVED FROM PER KERR ADDISON MINES LTD.

SAMPLE NO.	GOLD Oz. Per Ton	SILVER Oz. Per Ton	LEAD	ZINC			
A-56 1065 ✓		.41	.93	1.56			
1066 ✓		.53	1.33	2.00	663.7-668.0	4.3'	
1067 ✓		1.00	2.70	5.40	-673	5'	
1068 ✓		.15	.05	3.90	868.6-873.1	2.5'	
1069 ✓		1.41	3.98	6.48	872.1-874.9	(2.8')	
1070 ✓		.24	.50	1.32	874.9-879.3	(4.4')	
1071 ✓		.88	1.95	2.46	875.8-879.3	3.5	
1072 ✓		1.85	4.35	5.28	879.3-984.7	(5.4')	} 7.4' 5.33 2.01 9.8'
1073 ✓		2.21	4.50	5.40	889.7-886.6	(1.8')	
					916.6-991.0	(4.4')	
A 57 1101 ✓		.12	.12	.21			
1102 ✓		.62	1.45	2.70			
1103 ✓		1.03	2.30	4.44	116.3-117.1	(1.0')	
1104 ✓		.44	1.05	2.46			
1105 ✓		.06	.09	.13			
1106 ✓		.47	1.43	2.70			
1107 ✓		.83	1.50	3.00			
1108 ✓		.35	.93	1.76			
1109 ✓		.38	.84	.99			
1110 ✓		.50	1.33	2.52			
1111 ✓		.53	1.28	2.94			
1112 ✓		.59	1.35	3.06			
1113 ✓		.62	1.40	2.88			
1114 ✓		.24	.48	.42			
1115 ✓		.56	1.50	1.28			
1116 ✓		.44	.83	1.30			
1117 ✓		.59	1.13	1.50			
1118 ✓		1.00	2.33	3.18	809.3-816.7	(7.4')	
1119 ✓		.53	1.08	1.60			
1120 ✓		.59	1.35	2.40			
1121 ✓		.35	.90	1.24			
1122 ✓		.68	1.73	3.06			
1123 ✓		.59	1.25	1.54			
1124 ✓		.59	1.10	1.60			
1125 ✓		.38	.80	.74			
1126 ✓		.50	1.03	1.98			
1127 ✓		.29	.68	.68			
1128 ✓		.44	.93	.98			
1129 ✓		.62	1.50	2.64			
1130 ✓		1.00	2.10	3.06	883.3-888.2	(4.9')	
1131 ✓		.68	1.88	3.42	889.8-895.0	(6.2')	

ASSAYER. *S. Hayland Jr*
GEO. SPALDING

7059.8
993.7
056.3

DATE. NOVEMBER 27, 1974.

RECEIVED

ASSAY CERTIFICATE

FILE NO. 8816-19 & 8818-10

WHITEHORSE ASSAY OFFICE LTD.
BOX 4518 WHITEHORSE Y.T.

NOV 29 1974

KERR ADDISON MINES LTD.

PHONE 667 2694

SAMPLE RECEIVED FROM

KERR ADDISON MINES

SAMPLE NO.	PER		LEAD	ZINC				
	GOLD Oz. Per Ton	SILVER Oz. Per Ton						
<u>8816-19:</u>								
1144		1.47	3.45	3.90	993.7 - 1001.6	(7.9')		
1145 ✓		2.35	5.10	7.98	1001.6 - 1007.0	(5.4')	5.24	5.00 1.51
1146 ✓		1.06	1.95	4.20	-1016.0	(9.0')		22.3'
1147 ✓		.83	1.68	3.18	-1026			
1148 ✓		.65	1.33	2.94	-1033			
1149 ✓		.68	1.45	3.30	-1040			
1150 ✓		1.44	2.78	6.48	-1045.5	(5.5')	2.25	6.58 1.18
1151 ✓		.88	1.68	6.72	-1050.0	(4.5')		10.0'
1152 ✓		.21	.59	.78				
1153 ✓		.12	.23	.32				
1154 ✓		.59	1.58	1.56				
<u>1201-1208:</u>								
1201 ✓		3.09	9.45	7.20	436.5 - 442.5	(6.0')		
1202 ✓		2.06	4.73	6.60	448.5	(6.0')		
1203 ✓		1.09	1.83	4.68	453.0	(4.5')		
1204 ✓		2.35	4.05	7.08	456	(3.0')	5.47	6.00 2.128
1205 ✓		3.30	8.55	9.70	459.3	(3.3')		34'
1206 ✓		2.14	6.38	8.93	462	(2.7')		
1207 ✓		.59	1.23	1.34	466.5	(4.5')		
1208 ✓		2.35	7.40	4.26	470.5	(4.0')		
<u>8818-10:</u>								
922 ✓		2.65	5.93	11.11	848.9 - 854.5	(5.6')	4.03, 7.68, 1.87	
923 ✓		1.09	2.10	4.20	862.5 - 866	(5.5')	11.1	
924 ✓		.65	1.28	2.52	860 - 870	(10.0')	2.14, 4.06, 0.99	
925 ✓		.88	1.88	3.96	-880.2	10.2'		
926 ✓		.56	1.38	1.38	882.2	20'	48.3	
927 ✓		.74	1.65	3.18	885.3 - 891.3	6.0'		
928 ✓		1.00	2.40	4.02	891.3 - 897.2	(5.9')		
929 ✓		.50	1.23	2.34	-900.0	7.8'		
930 ✓		.09	.15	.28	918.9 - 924.3	10.4'		
931 ✓		.38	.85	1.36	-931.9	3.6'		

ASSAYER. A. Mayland
GEO. STANLEY

DATE. DECEMBER 4, 1974.

RECEIVED

ASSAY CERTIFICATE

FILE NO. 8822-26

DEC - 6 1974

WHITEHORSE ASSAY OFFICE LTD.
BOX 4518 WHITEHORSE Y.T.

KERR ADDISON MINES LTD.

PHONE 667 2694

SAMPLE RECEIVED FROM: KERR ADDISON MINES

SAMPLE NO.	GOLD Oz. Per Ton	SILVER Oz. Per Ton	LEAD	ZINC				
159 932		.35	.73	1.24	9335-936			
933		.41	1.03	1.98		5.1 x 3.01	15.351	25.973 = 2.7122
934		.24	.66	1.60		4.7 x 2.26	10.622	9.8
935		.12	.30	.44				
936		.21	.49	.94	952.4			
937		.21	.44	1.00	5122-10185	6.3 x 12.3		
938		.62	1.38	2.34		7.7 x 1.44		
939		.29	.65	.95		7.8 x 3.92		
940		.29	.65	1.24		4.1 x 1.6	6.56	
941		.29	.65	1.14		8.4 x 1.59	13.356	
942		.18	.63	.56		10.1 x 1.79	18.079	46.346
943		.03	.07	.09		4.9 x 1.17	5.681	28.5 = 1.2122
944		1.35	3.53	6.12				
945		.50	1.28	1.40				
946		.59	.90	.45				
947		2.94	6.15	10.38	-1081.6			
948		2.65	4.95	8.52	1081.6 - 1088	6.4		
949		3.06	8.43	14.39	-1093.7	5.7		7.66, 11.29, 3.02
950		3.53	5.70	11.67	-1101.4	6.4		23.4
951		.68	1.45	2.40	1105.3	4.9		
952		.18	.14	.72	1107.4	2.1		
953		.06	.19	.38	1108.0	7.8 x 0.86		.26
954		5.88	9.65	16.21	1115.4	7.0 x 0.57		3.99
955		.18	.05	.18	1115.4 - 116.5	1.1		4.85 = 0.606
956		5.74	14.61	19.44	1118.8	23		5.95, 8.80, 2.94
957		.06	.07	.12	1119.9	1.1		4.5
					1125.8	5.9		2.78, 4.17, 1.36
								10.0

Handwritten calculations and notes in the bottom left corner, including a vertical list of numbers (5.5, 9.5, 9.5, 10.5) and various arithmetic operations.

ASSAYER.

Handwritten signature: P. J. L. for

RECEIVED

ASSAY CERTIFICATE

DATE. DECEMBER 4, 1974.

DEC-61974

WHITEHORSE ASSAY OFFICE LTD.
BOX 4518 WHITEHORSE Y.T.

FILE NO. 6825-33

KERR ADDISON MINES LTD.

PHONE 667 2694

SAMPLE RECEIVED FROM

KERR ADDISON MINES

SAMPLE NO.	GOLD Oz. Per Ton	SILVER Oz. Per Ton	LEAD	ZINC	REMARKS		
<i>A57</i> 958 ✓		5.15	11.0	17.19	1125.8-1130.1	4.3	
959 ✓		1.55	2.33	2.52	1247.2-1252.3	4.1	
960 ✓		2.00	3.30	4.62	1255.1	3.8	
961 ✓		1.27	4.50	8.16	1260.7-1261.2	4.0	
962 ✓		2.15	5.10	8.28	1262.0-1270.5	3.5	4.18, 6.29, 1.96
963 ✓		.24	.68	.40	-1271.5	4.3	
964 ✓		2.94	6.30	9.41	-1278.7	6.9	
965 ✓		2.94	5.70	8.52	1280.5	5.8	
966 ✓		2.35	5.70	8.64	-1281.4	4.9	
967		1.29	2.10	1.84			
<i>A60</i> 1074 ✓		.12	.28	.24			
1075 ✓		2.29	5.16	7.08	330.7-335.8	5.1	
1076 ✓		3.59	7.50	9.71	-339.0	3.2	4.75, 5.35, 2.1
1077 ✓		2.21	3.53	3.78	-341.3	2.3	
1078 ✓		.09	.09	.12	-345.0	4.7	32.9
1079 ✓		.12	.15	.15	348.9	2.7	
1080 ✓		.85	1.60	.54	351.78	2.7	
1081 ✓		3.27	7.35	8.76	359.0	7.2	
1082 ✓		3.24	7.28	7.56	363.6	4.6	
1083 ✓		.12	.24	.25			
1084 ✓		1.27	3.68	3.18	365.7-370.0	(8.3)	4.36 4.03 1.76
<i>1085</i>		2.35	5.18	5.04	-381.0	(7.0)	
<i>A58</i> 1209 ✓		.91	1.58	.77	470.5-473.4	2.9	2 pp Zn
1210 ✓		.32	.37	.35	480.0	6.6	
1211 ✓		.83	2.10	.91	486.5	6.5	
1212 ✓		.38	.58	.71	495.0	8.5	
1213 ✓		.44	.54	.59	502.0	7.0	
1214 ✓		.18	.04	.02	509.0	7.0	
1215 ✓		.15	.03	.06	513.2	4.2	
1216 ✓		.12	.04	.17	515.0	1.8	
1217 ✓		.06	.03	.13	518	3.0	
1218 ✓		.15	.15	.03	524-527	3.0	
1219 ✓		.12	.22	.46	538	11.0	
1220 ✓		.03	.18	.25	544	6.0	

4.44 4.73 1.92 50.3

ASSAYER.

Ry loto fa

DATE. DECEMBER 9, 1974.

FILE NO. 8833- 27

ASSAY CERTIFICATE

WHITEHORSE ASSAY OFFICE LTD.

BOX 4518 WHITEHORSE Y.T.

PHONE 667 2694

SAMPLE RECEIVED FROM

KERR ADDISON MINES

SAMPLE NO.	GOLD Oz. Per Ton	SILVER Oz. Per Ton	LEAD	ZINC				
A-60 1085 ✓		2.35	5.18	5.04 ✓	see previous page: 374.0'-381.0' (7.0')			
- 1086 ✓		.56	.68	.51				
- 1087 ✓		.06	.19	.11				
- 1088 ✓		.38	.84	.77				
- 1089 ✓		.29	.78	.85				
1090		1.44	2.78	2.82 ✓	437.3'-437.7' (3.4') -444.4 (6.7') -449.5 (5.1')	} 4.65 4.32 1.68 15.2'		
1091		1.88	5.55	4.74 ✓				
1092		1.59	4.73	4.80 ✓				
- 1093		.21	.69	.99				
1094		5.00	11.48	17.35 ✓	-478.6-482.7' (4.1')	} expand to 10.1' wide } (3' either side.) i.e. 474.6 -> 485.7'	} 4.65 7.04 2.02 10.1'	
- 1095 ✓		.56	1.55	1.86				
- 1096 ✓		.59	1.13	1.02				
- 1097 ✓		TR	.07	.04				
- 1098 ✓		.03	.10	.36				
- 1099 ✓		TR	.02	.03				
- 1100 ✓		.47	1.30	1.14				
A-57 - 1155 ✓		.03	.05	.21				
- 1156 ✓		.03	.02	.06				
A-60 - 1221 ✓		.24	.39	.51				
1222		1.15	2.93	2.70				
- 1223 ✓		.44	1.00	.85				
- 1224 ✓		.29	.63	.32				
1225		1.29	3.68	2.88				
1226		.74	1.28	.74				
- 1227 ✓		.21	.25	.25				
- 1228 ✓		.80	1.63	.66				
1229		.09	.08	.03				

ASSAYER.

K. Howland jr
GEO. GRADUATE

DATE. DECEMBER 13, 1974.

FILE NO. 8838-16

ASSAY CERTIFICATE

WHITEHORSE ASSAY OFFICE LTD.
BOX 4518 WHITEHORSE Y.T.

PHONE 667 2694

SAMPLE RECEIVED FROM

KERR ADDISON MINES

SAMPLE NO.	GOLD Oz. Per Ton	SILVER Oz. Per Ton	LEAD	ZINC			
A.61 1968		.18	.39	.72			
✓ 1969		.50	1.40	2.46	794.6 - 798.0'	(3.4')	$3.4 \times 3.26 = 11.084$ $2.9 \times 5.95 = 17.255$ $1.92, 2.61, 0.65$ 20.39 $AV = 4.82$ 110.1
✓ 1970		1.18	1.93	4.02	795.0 - 800.9'	(2.9')	
✓ 1971		.32	1.05	1.66	800.9 - 804.1'	(3.8')	
✓ 1972		1.03	1.88	2.64	800.0 - 845.0'	(5.0')	
✓ 1973		.65	1.55	1.88	866.6' - 872.0'	(5.4')	5.4×3.43 18.582
✓ 1974		.95	1.85	3.00	881.1'	(9')	9.1×4.35 39.585
✓ 1975		.65	1.50	1.72		10.0' x 3.22	$= 32.2$ $6.1 \times 3.04 = 18.544$ $50.794 \rightarrow 3.15 \text{ Au}$ 0.62 Ag
✓ 1976		.56	1.28	1.76		6.1' x 3.04	
✓ 1977		.44	1.10	1.54		9.8' x 2.64	
A.A. ✓ 1978		.98	1.60	1.76			
✓ 1979		.18	.18	.39			
✓ 1980		.29	.40	.96			
✓ 1981		1.88	4.35	5.34	855.9' - 858.2'		
✓ 1982		.32	.63	.74			
✓ 1983		.29	.50	.52			

$4.5 \times 3.22 = 14.49$
 $6.1 \times 3.04 = 18.544$
 33.034

1.63
 2.23
 253.86
 1.72
 2.58
 6.20

1.6
 2.23
 3.83

ASSAYER.

R. Haydon GEO. SPALDIN

DATE. DECEMBER 13, 1974.

FILE NO. 8839-81

ASSAY CERTIFICATE

WHITEHORSE ASSAY OFFICE LTD.
BOX 4518 WHITEHORSE Y.T.

PHONE 667 2694

SAMPLE RECEIVED FROM

KERR ADDISON MINES

SAMPLE NO.	GOLD Oz. Per Ton	SILVER Oz. Per Ton	LEAD	ZINC			
<i>A-63</i> 1230 ✓		.77	1.73	1.48	258-262 (4)		
1231 ✓		.74	1.40	1.02	265 (3)		
1232 ✓		.88	2.15	2.64	267.5 (2.5)		
1233 ✓		1.21	3.15	1.90	273 (5.5)		
1234 ✓		.29	.37	.32	283 (10)		
1235 ✓		.15	.15	.12	293 (10)		
1236 ✓		.44	.37	.29	296 (3)		
1237 ✓		.15	.18	.15	306 (10)		
1238 ✓		.15	.14	.27	315 (9)		
1239 ✓		.10	.10	.38	317 (2)		
1240 ✓		.29	.50	1.10	323 (6)		
1241 ✓		.26	.47	1.38	325 (2)		
1242 ✓		1.82	5.63	7.20	325-326.4 (1.4)		
1243 ✓		.06	.05	.48	326.4-328-2 (1.2)		
1244 ✓		2.15	5.70	7.90	328.2-332-7 (6.5)	4.34	6.63 1.78
1245 ✓		2.03	4.13	6.72	-343.5 (6.2)		44.6'
1246 ✓		1.91	4.43	6.96	-348.5 (5.5)		
1247 ✓		2.00	4.58	6.48	-353.5 (5)		
1248 ✓		.83	1.68	2.00	-356.5 (5)		
1249 ✓		2.09	5.33	8.95	-364.0 (7)		
1250 ✓		.29	.87	1.60	-367.0 (3.0)		
1251 ✓		1.71	4.58	7.56	-369.6 (3.5)		
1252 ✓		.80	1.93	3.42	371-374 (3)		
1253 ✓		.18	.20	.40	376-385 (9)		
1254 ✓		.15	.15	.55	391.5 (6.5)		
1255 ✓		.59	1.23	2.46	398 (6.5)		
1256 ✓		.24	.27	.69	401.5 (3.5)		
1257 ✓		.10	.10	.29	409 (7.5)		
1258 ✓		.04	.09	.31	419 (10)		
1259 ✓		.03	.08	.23	426 (7)		
1260 ✓		1.71	4.50	6.24	426.0'-453.8' (6.8)		
1261 ✓		.50	1.40	1.78	438.5 (4.7)		
1262 ✓		.74	2.15	2.22	479-485.3 (6.3)		
1263 ✓		.15	.15	.17	495 (9.7)		
1264 ✓		.20	.27	.39	505 (10)		
1265 ✓		.18	.44	.75	477-479 (2)		

ASSAYER. L. Hayland Jr. GEO. SPALDING

DATE. DECEMBER 13, 1974.

ASSAY CERTIFICATE

FILE NO. 8834-58
COMPOSITES

WHITEHORSE ASSAY OFFICE LTD.
BOX 4518 WHITEHORSE Y.T.

PHONE 667 2694

SAMPLE RECEIVED FROM

KERR ADDISON MINES

SAMPLE NO.	GOLD Oz. Per Ton	SILVER Oz. Per Ton	COPPER				
1	174-177	.04	.12				
2	179-182	.02	.21				
3	187-195	.02	.13				
4	319-321	.03	.36				
5	332-337	.02	.13				
6	341-346	.02	.14				
7	349-355	.02	.14				
8	362-366	.02	.12				
9	371-374	.01	.07				
10	404-423	.02	.14				
11	198-200 + 301	.02	.13				
12	380-385	.03	.19				
13	428-429	.02	.18				
14	437-441	.04	.33				
15	442-444	.04	.31				
16	446-448	.02	.18				
17	449-453	.02	.18				
18	471-479	.01	.07				
19	497-498	.04	.15				
20	505	.02	.20				
21	400 + 527	.01	.03				
22	529-532	.01	.04				
23	538-541	.01	.07				
24	544-549	.02	.08				
25	572-574	.02	.29				
26	611-616	.01	.04				
27	618-620	.01	.05				
28	625-626	.02	.11				
29	627-628	.03	.19				
30	649-651	.03	.21				
31	653-657	.02	.17				
32	670	.02	.16				
33	683-700	.02	.22				
34	717-718	.01	.12				
35	720-721	.02	.15				
36	731-734	.01	.20				
37	747-754	.02	.19				
38	757-759	.02	.17				
39	786-788	.02	.16				
40	794-800	.02	.09				
41	801-802	.01	.10				
42	804-810	.02	.17				
43	816-819	.02	.13				
44	229-230	.02	.14				
45	862-863	.02	.05				
46	866-867	.02	.05				

ASSAYER.

K. Hayward Jr
GEO. SMITH

ASSAY CERTIFICATE

WHITEHORSE ASSAY OFFICE LTD.
BOX 4518 WHITEHORSE Y.T.

PHONE 667 2694

DECEMBER 13, 1974.

LE NO. 8834-58
COMPOSITES

KERR ADDISON MINES

SAMPLE RECEIVED FROM

SAMPLE NO.	GOLD Oz. Per Ton	SILVER Oz. Per Ton	COPPER				
47 868-872	.03		.18				
48 895-900 + 580-584	.02		.12				
49 592-594	.02		.16				
50 597-600 + 901	.03		.18				
51 904-908	.03		.15				
52 915-917	.01		.34				
53 918	.02		.05				
54 1016-1022	.02		.07				
55 1028-1050	.02		.07				
56 1052-1064	.02		.11				
57 1069-1070	.02		.13				
58 1072-1073	.03		.19				
Average = 0.021oz Au/ton			Average = 0.148% Cu				

ASSAYER. *K. Hayward for*
GEO. STRADING

DATE. DECEMBER 13, 1974.

ASSAY CERTIFICATE

FILE NO. 8839-81

WHITEHORSE ASSAY OFFICE LTD.
BOX 4518 WHITEHORSE Y.T.

PHONE 667 2694

SAMPLE RECEIVED FROM

KERR ADDISON MINES

SAMPLE NO.	GOLD Oz. Per Ton	SILVER Oz. Per Ton	LEAD	ZINC			
<i>A62</i> 984		.29	.33	.18			
985		.85	2.10	2.40	244 - 248.0 (4.0)	5.97	5.44 2.40
986		4.47	11.13	9.51	-251.0 (3.4)		7.0'
987		2.71	7.53	6.48	267 - 270.5 (3.5)	9.08	6.32 3.12
988		3.35	9.93	6.24	-277.5 (6.5)		10.0'
989		.26	.62	.78			
990		3.09	6.68	11.05	415.5 - 422.0 (6.5)		
991		2.50	5.60	10.25	-428.0 (6.0)		
992		.25	.18	.62	428.0 - 432.3 (4.3)	4.67	8.89 2.35
993		1.47	2.78	5.88	432 - 436.2 (3.9)		37.8'
994		2.47	4.65	8.94	-441.7 (5.5)		
995		2.71	4.80	10.16	-447.2 (5.5)		
996		3.03	5.94	11.82	-453.3 (6.1)		
997		.35	1.12	1.14			
998		1.32	3.08	4.26	572.6' - 582.2'		
999		.56	.18	.45			
1000		.32	.27	.72			
<i>A.3A</i> 1157		.32	.75	1.94			
1158		.29	.83	1.02			
1159		.24	.79	.56			
1160		.26	.63	1.20			
1161 ✓		.38	.87	1.44			
1162 ✓		.41	.75	2.58			
1163		.29	.69	1.60			
1164		1.76	3.68	9.30	811 - 816 (5')		
1165 ✓		.59	1.30	1.98			
1166 ✓		.59	1.38	1.86			
1167		.44	1.03	1.32			
<i>A62</i> 1168 ✓		.35	.49	.80			
1169 ✓		.29	.27	1.30			
1170		.26	.53	.76			
1171		.44	1.43	1.36			
1172		.94	3.75	4.50	804.6' - 808.6'		
1173		.03	.04	.14			
1174		.06	.48	.72			
1175		.03	.10	.14			
1176		1.32	3.08	4.02	829.9' - 836.2'		
1177		.32	.68	1.12			
1178		.88	1.98	1.36			
1179		2.24	5.55	6.24	849.9' - 855.2' (5.3)	3.99	4.60 1.67
1180		.94	1.95	2.46	-860.0' (4.8')		11.1'
1181		.38	.68	.78			
1182 ✓		.24	.23	.24			
1183 ✓		1.03	2.50	1.38			
1184		.24	.27	.62			

ASSAYER.

L. H. ...

GEO. SPALDING

DATE. JANUARY 20, 1975.

FILE NO. 8844-13

ASSAY CERTIFICATE

WHITEHORSE ASSAY OFFICE LTD.
BOX 4518 WHITEHORSE Y.T.

PHONE 667 2694

SAMPLE RECEIVED FROM

KERR ADDISON MINES

SAMPLE NO.	GOLD Oz. Per Ton	SILVER Oz. Per Ton	LEAD	ZINC				
<i>A-63</i>								
1266 ✓		.97	2.20	2.40	505-513.7 (8.7)			
1267 ✓		.10	.13	.22	522 (8.3)			
1268 ✓		.77	1.88	1.66	530.4 (8.4)			
1269 ✓		.59	1.10	1.40	536.1 (8.7)			
1270 ✓		.74	1.65	1.62	541 (9.9)			
1271 ✓		.83	1.85	1.56	546 (5.4)			
1272 ✓		.18	.23	.25	549 (2.7)	>		
1273 ✓		1.62	4.65	5.22	552.7 (3.6)	>		
1274 ✓		.10	.12	.13	555.7 (3)	>		
1275 ✓		.68	1.70	2.58	564 (8.3)	>		
1276 ✓		.15	.17	.40	568.3 (4.3)			
1277 ✓		.04	.05	.10	578 (9.7)			
1278 ✓ ✓		.06	.07	.12	583 (5.1)			

Assays entered onto Vancouver office DD logs only

Jan 24/75



ASSAYER.

K. Hoyte

GEO. SPALDING