

Gr - Mixed Zones

Pg 1.

018827

			Pb	Zn.	Ag.
A-1	853.0 - 863.7	10.7'	Mixed.		4.9 <hr/> 60
A-4	481.5 - 491.5	10.0'	Mixed.		
	515.0 - 527.0	12.0'	Mixed.		
	537.5 - 562.3	24.8'	Mixed.		
	656.0 - 682.5	26.5'	5.51	8.60	3.31
A-5	420.0 - 426.0	6.0'	10.60	9.62	3.84
	508.0 - 591.8	83.8	3.92	8.54	1.99
A-6	No INTERSECTIONS				
A-8	238.0 - 267.0	29.0'	Mixed		
	306.8 - 322.0	15.2	2.47	5.65	1.04
	583.5 - 592.5	9.0	3.23	6.11	1.48
A-9	373.8 - 410.0	36.2	Mixed		
	410.0 - 416.0	6.0	5.55	7.92	0.80
	434.0 - 479.0	45.0'	4.32	7.15	2.25
A-10	518.0 - 623.0	105.0'	4.39	6.75	1.95
	623.0 - 730.0	107.0'	weak mixed.		
	730.0 - 756.0	26.0'	5.14	8.03	2.63
	756.0 767.0 - 775.4	8.4'	3.00	6.72	1.82
	775.4 - 802.0 802.0	26.6'	Mixed		
	802.0 - 815.0	13.0'	4.50	6.27	2.24

Pb Zn Ag.

A-11	379.0 - 387.0	8.0'	6.00	6.84	2.70
	387.0 - 453.5	66.5'	Mineralized		
	493.5 - 506.5	13.0'	4.55	3.87	0.87
	584.0 - 599.0	15.0'	7.37	11.45	3.92
	693.0 - 704.0	11.0'	Mineralized		
	728.0 - 736.5	8.5'	Mineralized		
	736.5 - 745.0	8.5'	3.38	5.28	1.92

A-12	745.0 - 755.0	10.0'	Mineralized		
	755.0 - 763.0	8.0'	2.33	7.80	1.26
	811.0 - 853.5	42.5'	Mineralized		
	895.0 - 1044.5	149.5'	Mineralized		
	1044.5 - 1054.5	10.0'	4.73	6.96	2.80

A-13	106' <u>ovbd.</u> 133.5 - 145.5	12.0'	Mineralized		
	145.5 - 202.0	56.5'	5.38	4.80	2.22
	202.0 - 219.0	17.0'	Mineralized		
	398.0 - 410.5	12.5'	Mineralized		
	428.0 - 448.0	20.0'	Mineralized.		

A-14	632.0 - 636.0	4.0'	Mineralized		
	873.0 - 896.0	23.0'	Mineralized		
	896.0 - 905.0	9.0'	6.53	6.96	2.67
	905.0 - 942.0	37.0'	Mineralized.		

109
282
391

			Pb	Zn	As.
A-15	424.4 - 433.9	8.5'		Miscalc'd	
	453.0 - 502.0	49.0'	4.25	4.00	2.11
	520.0 - 570.0	50.0'		Miscalc'd	
	570.0 - 580.0	10.0'	3.60	5.58	1.42
	580.0 - 623.0	43.0'		Miscalc'd.	
A-16	761.0 - 761.0 861.0	100.0'		Miscalc'd	
	861.0 - 888.0	27.0'	2.33	3.85	1.14
	888.0 - 903.0	15.0'		Miscalc'd	
A-17	689.0 - 728.0	39.0'		Miscalc'd	
	745.0 - 778.0	33.0'		Miscalc'd	
	778.0 - 784.0	6.0'	6.38	7.92	2.56
	784.0 - 797.0	13.0'		Miscalc'd	
	797.0 - 802.0	5.0'	3.15	5.04	1.32
	802.0 - 846.5	44.5'		Miscalc'd.	
A-18	1021.0 - 1043.0	22.0'	5.62	9.73	3.16
	1043.0 - 1057.0			Miscalc'd	
	1057.0 - 1066.0	9.0'	5.01	8.62	2.79
	1066.0 1071.0 - 1113.0	42.0'	2.64	4.85	1.69
	1113.0 - 1120.0			Miscalc'd.	

A 19

		Pb	Zn	Ag.
335.8 - 345.6	9.8		Miscalyid	
345.6 - 355.0	9.4	6.68	5.64	3.18
442.0 - 467.3	25.3		Miscalyid	
467.3 - 471.3	4.0	7.35	9.36	4.08
471.3 - 493.0	21.7		Miscalyid	
493.0 - 500.5	7.5	4.95	6.96	1.76
500.5 - 510.0	9.5		Miscalyid	
521.4 - 531.3	9.9'		Miscalyid	
531.3 - 583.3	52.0'	3.56	6.23	1.76
601.6 - 603.3	1.7'	2.18	5.10	1.48
637.0 - 673.5	36.5	5.09	8.12	2.39
673.5 - 711.1	37.6		Miscalyid	
711.1 - 718.5	7.4'	2.85	4.02	0.98
718.5 - 753.0	34.5		Miscalyid	

A-20

603.0 - 632.0			Miscalyid	
632.0 - 637.0	5.0'	2.85	5.52	1.04
637.0 - 667.0			Miscalyid	
667.0 - 676.0	9.0'	4.08	6.07	1.82
689.0 - 693.0	4.0	4.35	6.72	2.12
693.0 - 703.0	10.0		Miscalyid	
703.0 - 733.0	30.0	3.36	6.87	1.99
733.0 - 759.0	26.0'		Miscalyid.	
778.0 - 783.0	5.0'		Miscalyid	
783.0 - 789.0	6.0'	3.15	5.28	2.46
812.0 - 826.0	14.0'	4.20	4.86	1.99
843.0 - 848.0	5.0'		Miscalyid.	

		Pb	Zn	Ag.
A-21	328.4 - 331.6	3.2		Unanalyzed.
	331.6 - 378.0	46.4	4.72	7.75 2.02
	378.0 - 404.2	26.2		Unanalyzed.
	434.0 - 439.0	5.0'		Unanalyzed
	548.0 - 565.5	17.5'		Unanalyzed
	590.0 - 594.5	4.5'		Unanalyzed
	594.5 - 657.0	62.5	4.38	7.56 1.90
	657.0 - 667.3	10.3'		Unanalyzed.
	689.4 - 814.8	125.4		Unanalyzed.

A-22	506.0 - 507.6	1.6				Unanalyzed.
	571.5 - 593.8	22.3				Unanalyzed.
	593.8 - 606.2	12.4'	5.42	6.05	2.44,	
	606.2 - 619.1	12.9				Unanalyzed.
	754.2 - 798.5	44.3'	3.42	5.97	1.75	
	798.5 - 810.4	11.9'				Unanalyzed
	810.4 - 820.2	9.8'	3.83	6.96	1.52	
	820.2 - 828.6	8.4'				Unanalyzed.
	828.6 - 844.6	16.0'	4.35	7.87	1.89	
	887.6 - 900.4	12.8'				Unanalyzed
	900.4 - 914.8	14.4'	5.31	10.36	2.82	
	914.8 - 918.0	3.2'				Unanalyzed.
	1125.1 - 1170.2	45.1'	4.27	7.23	2.16	
	1170.2 - 1191.8	21.6'				Unanalyzed.

Pb	Zn	Ag
2.81	5.28	1.48
<hr/>		
90.4'		

			Pb	Zn	Ag.
A-23	150' <u>ovbd.</u>				
	256.0-462.0	206.0	3.82	7.64	1.80
	462.0-578.0	116.0'		Mineralized	
	772.5-779.5	7.0'	4.80	6.48	1.76
	785.5-810.0	24.5'		Mineralized	
	862.0-876.0	14.0'		Mineralized	
	904.5-909.0	4.5'		Mineralized	
	913.5-920.0	7.0'		Mineralized.	
A-24	458.7-493.6	34.9	4.60	3.98	1.93
	581.5-585.3	3.8		Mineralized	
	585.3				
	585.3 - 669.7	84.4	3.99	6.46	1.73 *
	669.7-711.0	41.3		Mineralized	
	711.0-716.6	5.6	3.30	6.12	1.24 *
	716.6-748.0	31.4		Mineralized	
	748.0-758.0	10.0	2.90	5.60	2.08 ✓
	758.0-767.0	9.0		Mineralized	
	819.0-826.4	7.1		Mineralized.	
	826.1-831.6	5.5	4.65	8.88	2.82
	831.6-844.2	12.6		Mineralized.	
	1078.8-1127.4	48.6	6.11	10.60	2.82
	1127.4-1132.4	5.0		Mineralized.	

A-25

No INTERSECTIONS.

	153' - <u>ovbd</u>		Pb	Zn	Ag
A. 26	153.0 - 330.0	177.0'	4.45	8.64	2.18
	330.0 - 344.5	14.5'		Miscalc'd	
	344.5 - 348.5	4.0	7.05	8.04	2.85
	348.5 - 482.7	134.2		Miscalc'd (421.5 - 482.7 narrow)	
	595.5 - 601.4	5.9'		Miscalc'd	
	684.6 - 694.7	10.1'	3.39	4.65	1.78

A. 27	525.8 - 528.0	2.2		Miscalc'd.	
	528.0 - 557.0	29.0 29.0	2.66	4.99	1.54
	557.0 - 646.0	89.0		Miscalc'd.	
	646.0 - 658.3	12.8'	2.69	5.38	1.32
	658.3 - 658.3 ^{656.0} 706.0	47.7		Miscalc'd.	
	706.0 - 739.0	33.0	4.74	5.39	2.10
	739.0 - 769.0	30.0		Miscalc'd.	
	847.0 - 943.0			2	
	1068.5 - 1124.5			2	
	847.0 - 920.0	73.0'		Miscalc'd	
	920.0 - 925.0	5.0'	3.00	4.38	1.15
	925.0 - 943.3	18.3'		Miscalc'd	
	1068.5 - 1089.5	21.0'		Miscalc'd	
	1089.5 - 1109.5	20.0'	4.09	7.98	1.94
	1109.5 - 1124.5	15.0'		Miscalc'd	

A. 28	281.0 - 303.8	22.8'	615% Carbide		3.22
				Miscalc'd.	

A. 30	474.2 - 529.3	55.1'		Miscalc'd - (narrow)	
	545.9 - 561.0	15.1	3.20	7.03	1.49
	561.0 - 581.6	20.6		Miscalc'd.	
	581.6 - 606.8	25.2	3.14	5.80	1.50
	606.8 - 617.9	11.1		Miscalc'd.	
	617.9 - 626.0	8.1	3.45	4.92	1.50
	626.0 - 638.8	12.8		Miscalc'd	
	638.8 - 656.6	17.8	2.77	4.21	1.21
	656.6 - 664.0	7.4		Miscalc'd	
	701.4 - 718.2	16.8'	5.47	9.21	2.43
	718.2 - 721.0	2.8'		Miscalc'd	
	721.0 - 738.3	17.3'	7.15	12.2	3.27
	833.9 - 840.1	6.2	3.75	7.68	1.68

EST GRADES GRUM.

A-27 1068.5 - 1090.0 Miscelized
1090.0 - 1124.5 8% Cobind.

A-28 281.0 - 303.0 22.0' 10% Cobind. 15% Cobind
383.0 - 387.0 4.0' Miscelized.
702.0 - 705.0 3.0' Miscelized.
705.0 - 727.0 22.0' 7% Cobind.
727.0 - 749.0 22.0' Miscelized.
829.0 - 834.0 5.0' Miscelized
849.0 - 854.0 5.0' Miscelized.
(383-737 Massive Sulphide).

A-29 1209.0 - ~~1322~~ 1333.0 124.0' Miscelized.
1333.0 - 1345.0 12.0' 9% Cobind.

A-30 474.0 - 529.0 55.0' 9% Cobind.
545.0 - 552.0 7.0' Miscelized.
552.0 - 561.0 9.0' 11% Cobind.
561.0 - 582.0 21.0' Miscelized.
582.0 - 599.0 17.0' 8% Cobind.
599.0 - 645.0 46.0' Miscelized (near ore)
645.0 - 664.0 19.0' Miscelized.
702.0 - 741.0 39.0' 14% Cobind

See
 Amongst
 ↗

A-31	378.5-380.5	2.0'	12% Combined. U
	404.5-408.0	3.5'	Mined.
	438.3-446.3	8.0'	Mined (near ore).
	553.2-571.0	17.8'	8% Combined.

A-32	513.0-521.5	8.5'	9% Combined.
	931.5-940.2	8.7'	8% Combined.
	940.2-980.5	40.3'	Mined.
	980.5-993.0	12.5'	9% Combined.
	993.0-1016.5	23.5'	Mined
	1016.5-1076.5	60.0'	6% Combined.

A-33 — NO REPORT 154 vubd.

A-34 — NO REPORT

A-35	521.0-536.5	15.5'	7-8% Combined.
	536.5-		
	521.0-561.9	40.9'	7-8% Combined.

See add page

Sept 12/74

Grum Program - Est.

- A-33 154' orbd. - at 718' and drilling.
- A-34 No progress. machine under repairs.
- A-35
- ~~42' ~~drilled zone~~ zone (week) in upper part of hole.~~
 - 521.0 - 521.9 40.9 7-8% Carbide
 - 937.0 - 952.0 15' 5% Carbide.
 - 1068 - 1084 16' 1% Carbide.
 - 1084 - 1108 24' 2-3% Carbide.
 - 1108 - 1122 14' 6% Carbide.
 - 1122 - 1127 5' 1-2% Carbide.
 - 1127 - 1138 11' 10-12% Carbide.
 - 1138 - 1150 12' 4-5% Carbide.

A-37

~~36W 4S~~ 93.5' orbd.

- 215.0 - 231.0 4-6% Carbide
- 234.0 - 243.0 6-8% Carbide (MS.)
- 243.0 - 276.0 10-15% Carbide.
- 277.0 - 281.0 1% Carbide.
- 281.0 - 283.5 15-20% Carbide.
- 283.5 - 291.1 6-7% Carbide.
- 297.7 - 316.0 5-6% Carbide.
- 316.0 - 323 7-8% Carbide.

drilling,