

018839

31/08/77 GRUM PROJ.

Diamond
Drill

Log

Surface

HOLE NO: A-1
HOLE LENGTH: 312.72

LATITUDE: 10579.43
DEPARTURE: 7323.27
ELEVATION: 1307.45

AZIMUTH: 0.00 ✓
DIP: -90.00 ✓

INTERVAL		ASSAYS		
FROM	TO	PB %	ZN %	AG GM/TON
0.00	259.99	N/A	N/A	N/A
259.99	263.26	1.45	1.28	20.23
263.26	312.72	N/A	N/A	N/A

HOLE NO: A-4
 HOLE LENGTH: 314.86

LATITUDE: 10719.32
 DEPARTURE: 7475.03
 ELEVATION: 1297.38

AZIMUTH: 0.00
 DIP: -90.00

DIP TESTS:	DEPTH	DIP	AZIMUTH
	64.01✓	-90.00✓	0.00✓
	✓91.44	-87.00✓	74.50✓
	✓152.40	-83.30✓	34.50✓
	✓213.36	-84.30✓	42.20✓
	✓259.08✓	-83.00✓	319.50✓

1129.54

INTERVAL		ASSAYS			
FROM	TO	PB %	ZN %	AG GM/TON	
0.00	146.76	N/A	N/A	N/A	
146.76	149.81	.10	.16	2.06	
149.81	156.97	N/A	N/A	N/A	
156.97	160.63	.30	.25	4.11	
160.63	163.83	N/A	N/A	N/A	
163.83	165.35	3.00	2.62	55.53	
165.35	166.88	2.25	2.04	53.48	
166.88	168.25	.20	.20	13.03	
168.25	169.77	.94	.90	.00	
169.77	171.39	4.05	3.24	.00	
171.39	199.95	N/A	N/A	N/A	
199.95	201.47	6.16	8.75	126.15	
201.47	203.00	7.50	10.10	126.15	
203.00	204.52	5.96	10.80	129.24	
204.52	205.89	7.19	13.98	151.17	
205.89	208.03	2.23	3.84	60.33	
208.03	244.57	N/A	N/A	N/A	
244.57	245.67	1.60✓	1.76✓	33.59	.98
245.67	256.55	N/A	N/A	N/A	-
256.55	259.35	.18✓	.39✓	6.17	.18
259.35	260.88	.40✓	.96✓	9.94	.29
260.88	261.58	4.35✓	5.34✓	64.45	.88
261.58	261.95	.63✓	.74✓	28.11	.32
261.95	283.71	N/A	N/A	N/A	-
283.71	285.99	.50✓	.52✓	9.94	.29
285.99	314.86	N/A	N/A	N/A	-

AG
 02/TON

SPECIFIC MOORE BUSINESS FORMS 4

HOLE NO: A-5 LATITUDE: 10786.52 AZIMUTH: 0.00 ✓
HOLE LENGTH: 180.53 DEPARTURE: 7520.97 DIP: -90.00 ✓
ELEVATION: 1303.85

INTERVAL		ASSAYS						
FROM	TO	PB	ZN	AG	AG	AU	CU	
		%	%	GM/TON	02/TON	02/TON	%	
0.00	128.02	N/A	N/A	N/A				
128.02	129.84	10.60 ✓	9.62 ✓	131.64	3.84	.01 .34	.20	
129.84	154.84	N/A	N/A	N/A				
154.84	156.21	.68 ✓	1.80 ✓	4.11	.12	RR .00	.04	
156.21	157.58	.15 ✓	.38 ✓	2.74	.08	TR .00	.02	
157.58	158.95	.25 ✓	.24 ✓	1.37	.04	TR .00	.06	
158.95	160.48	1.03 ✓	1.44 ✓	12.34	.36	.01 .34	.07	
160.48	161.70	6.50 ✓	21.50 ✓	113.81	3.32	.01 .34	.25	
161.70	163.68	4.70 ✓	22.90 ✓	58.96	1.72	.01 .34	.16	
163.68	165.35	9.20 ✓	15.50 ✓	176.20	5.14	.02 .69	.32	
165.35	165.96	.38 ✓	.38 ✓	9.60	.28	.01 .34	.06	
165.96	166.51	3.98 ✓	8.06 ✓	61.02	1.78	.02 .69	.05	
166.51	169.62	.38 ✓	.62 ✓	2.74	.08	.005 .17	.06	
169.62	170.47	4.05 ✓	6.85 ✓	77.47	2.26	.02 .69	.19	
170.47	171.75	6.45 ✓	12.30 ✓	104.90	3.06	.02 .69	.16	
171.75	173.13	6.60 ✓	13.10 ✓	152.20	4.44	.02 .69	.28	
173.13	174.32	5.78 ✓	9.24 ✓	149.46	4.36	.04 1.37	.29	
174.32	175.87	5.85 ✓	9.03 ✓	82.27	2.40	.04 1.37	.33	
175.87	177.09	6.90 ✓	9.10 ✓	141.23	4.16	.04 1.37	.34	
177.09	178.77	9.20 ✓	17.40 ✓	125.46	3.66	.02 1.69	.18	
178.77	180.38	1.13 ✓	2.28 ✓	16.45	.48	.01 .34	.05	
180.38	180.53	N/A	N/A	N/A				

SPECIFIC TO MINOR BUSINESS FORMS 4

HOLE NO: A-8 LATITUDE: 11144.64 AZIMUTH: 0.00 ✓
 HOLE LENGTH: 232.56 DEPARTURE: 7537.27 DIP: -90.00 ✓
 ELEVATION: 1319.14

DIP TESTS: DEPTH DIP AZIMUTH
 60.96 -83.30 130.10
 121.92 -79.30 122.10
 182.88 -75.00 142.40

~~152.9 + 1091.44~~

INTERVAL		ASSAYS			
FROM	TO	PB %	ZN %	AG GM/TON	AG OZ/TON
0.00	72.54	N/A	N/A	N/A	-
72.54	74.68	.98 ✓	1.12 ✓	13.71	.40
74.68	76.20	.90 ✓	1.26 ✓	16.45	.48
76.20	80.16	.80 ✓	.90 ✓	10.97	.32
80.16	81.38	.21 ✓	.08 ✓	2.74	.08
81.38	93.51	N/A	N/A	N/A	-
93.51	95.25	2.03 ✓	6.08 ✓	37.02	1.08
95.25	96.93	2.48 ✓	4.62 ✓	31.54	.92
96.93	98.15	3.08 ✓	6.48 ✓	39.76	1.16
98.15	98.91	1.93 ✓	2.28 ✓	28.80	.84
98.91	177.85	N/A	N/A	N/A	-
177.85	180.59	3.23 ✓	6.11 ✓	50.73	1.48
180.59	232.56	N/A	N/A	N/A	-

K

4.08

~~1319.14~~

HOLE NO: A-9 LATITUDE: 10896.01 AZIMUTH: 0.00 ✓
 HOLE LENGTH: 231.95 DEPARTURE: 7632.18 DIP: -90.00 ✓
 ELEVATION: 1312.92

DIP TESTS:	DEPTH	DIP	AZIMUTH
	✓ 60.96	-86.00 ✓	133.20 ✓
	✓ 121.92	-80.00 ✓	121.20 ✓
	✓ 182.88	-79.00 ✓	114.20 ✓
	✓ 219.46	-80.00 ✓	93.20 ✓

INTERVAL	ASSAYS
FROM TO	PB ZN AG AG
	% % GM/TON OZ/TON
0.00 113.93	N/A N/A N/A -
113.93 124.60	1.48 3.71 33.94 -
124.60 124.97	N/A N/A N/A -
124.97 126.80	5.55 ✓ 7.92 ✓ 27.42 2.90
126.80 132.28	N/A N/A N/A -
132.28 146.00	4.32 7.15 77.13 -
146.00 231.95	N/A N/A N/A -

99.41

			02/TON	AU	Cu
				02/TON	
0.00	113.93	N/A	N/A	N/A	N/A
113.93	115.45	1.18	3.36	.64 21.94	.01 .34 .09
115.45	116.98	.95	2.28	.32 10.97	.005 .17 .03
116.98	118.51	2.23	5.28	1.82 62.39	.02 .69 .03
118.51	120.03	2.50	5.40	1.67 57.25	.01 .34 .04
120.03	121.55	2.03	4.20	1.12 38.39	.01 .34 .05
121.55	123.08	.98	1.40	.56 19.20	.01 .34 .03
123.08	124.60	2.00	4.02	.80 27.42	.01 .34 .06
124.60	124.97	N/A	N/A	N/A -	N/A - N/A
124.97	126.80	5.55	7.92	2.90 99.41	.02 .69 .06
126.80	132.28	N/A	N/A	N/A -	N/A - N/A
132.28	133.81	2.85	6.12	1.68 57.59	.01 .34 .08
133.81	135.33	5.55	10.52	2.80 95.98	.04 1.37 .12
135.33	136.86	7.50	10.63	2.78 95.30	.02 .69 .09
136.86	138.38	7.35	11.88	3.01 103.18	.03 1.03 .10
138.38	139.90	2.45	5.16	2.18 74.73	.02 .69 .05
139.90	141.43	1.90	4.26	1.62 55.53	.02 .69 .04
141.43	142.95	2.93	7.08	1.50 51.42	.02 .69 .05
142.95	144.48	4.28	8.50	2.86 98.04	.02 .69 .10
144.48	146.00	4.13	6.24	1.82 62.40	.02 .69 .07

DIAMOND DRILL LOG MA

STER FILE

HOLE NO: A-10
HOLE LENGTH: 264.57

LATITUDE: 10826.53
DEPARTURE: 7482.81
ELEVATION: 1309.47

AZIMUTH: 0.00
DIP: -90.00

DIP TESTS:	DEPTH	DIP	AZIMUTH
✓	60.96	-85.15 ✓	60.50 ✓
✓	121.92	-82.30 ✓	72.50 ✓
✓	182.88	-84.30 ✓	72.20 ✓
✓	243.84	-88.00 ✓	(104.20) / 140.00

INTERVAL		ASSAYS				
FROM	TO	PB	ZN	AG	AG	
		%	%	GM/TON	OZ/TON	
0.00	157.89	N/A	N/A	N/A	-	
157.89	189.89	4.39	6.75	66.85		
189.89	222.50	N/A	N/A	N/A		
222.50	230.43	5.14	8.03	90.16		
230.43	233.78	N/A	N/A	N/A		
233.78	236.34	3.00	6.72	62.39		
236.34	237.44	N/A	N/A	N/A		
237.44	238.66	1.73	3.12	34.97		
238.66	239.27	N/A	N/A	N/A		
239.27	240.06	5.25	13.80	95.98		
240.06	244.45	N/A	N/A	N/A		
244.45	248.41	4.50	6.27	76.79		
248.41	264.57	N/A	N/A	N/A		
				AG	AO	Cu
				OZ/TON	OZ/TON	%
0.00	158.04	N/A	N/A	N/A	N/A	N/A
158.04	159.56	5.55	14.79	3.06	104.90	.02 .69 .24
159.56	161.09	4.35	6.96	2.14	73.36	.02 .69 .14
161.09	162.61	2.55	2.76	1.56	53.48	.04 1.37 .24
162.61	164.13	3.08	4.26	1.48	50.73	.04 1.37 .28
164.13	165.66	6.38	11.45	3.12	106.95	.04 1.37 .10
165.66	167.18	5.63	13.50	2.82	96.67	.02 .69 .10
167.18	168.71	2.85	7.44	1.32	45.25	.01 .34 .04
168.71	170.23	1.08	2.58	1.22	41.82	.02 .69 .27
170.23	171.60	3.83	7.20	2.68	91.87	.04 1.37 .13
171.60	173.13	7.65	13.86	4.48	153.57	.04 1.37 .29
173.13	174.65	8.70	16.97	3.86	132.32	.06 2.06 .22
174.65	176.17	7.80	14.04	3.18	109.01	.02 .69 .15
176.17	177.70	4.35	9.68	1.90	65.13	.02 .69 .07
177.70	180.75	1.63	3.48	.68	23.31	.01 .34 .03
180.75	183.79	3.15	5.64	1.04	35.65	.01 .34 .04
183.79	186.84	5.25	3.96	1.50	51.42	.02 .69 .10
186.84	189.89	4.20	1.24	1.10	37.71	.02 .69 .08
189.89	199.03	N/A	N/A	N/A	N/A	- N/A
199.03	206.65	.35	.74	.16	5.48	.005 .17 .07

HOLE NO: A-11
 HOLE LENGTH: 249.94

LATITUDE: 10696.65
 DEPARTURE: 7521.19
 ELEVATION: 1292.05

AZIMUTH: 0.00
 DIP: -90.00

DIP TESTS:	DEPTH	DIP	AZIMUTH
	✓60.96	-85.20 ✓	63.50 ✓
	✓121.92	-82.30 ✓	74.20 ✓
	✓182.88	-81.30 ✓	53.20 ✓
	✓237.74	-78.00 ✓	80.50 ✓

INTERVAL		ASSAYS						
FROM	TO	PB	ZN	AG	AG	AO	Cu	
		%	%	GM/TON	OZ/TON	gm/tonne		
0.00	115.52	N/A	N/A	N/A	-	-	-	
115.52	117.96	6.00 ✓	6.84 ✓	92.56	2.70	.69	.12	
117.96	119.02	N/A	N/A	N/A	-	-	-	
119.02	120.55	2.10 ✓	2.58 ✓	43.88	1.28	.34	.15	
120.55	121.46	N/A	N/A	N/A	-	-	-	
121.46	122.77	1.95 ✓	1.26 ✓	38.39	1.12	.34	.21	
122.77	123.90	N/A	N/A	N/A	-	-	-	
123.90	127.71	.53 ✓	.40 ✓	9.60	.28	.17	.07	
127.71	133.20	N/A	N/A	N/A	-	-	-	
133.20	134.42	1.30 ✓	.58 ✓	15.77	.46	.00	.08	
134.42	138.23	.28 ✓	.27 ✓	7.54	.22	.00	.03	
138.23	150.42	N/A	N/A	N/A	-	-	-	
150.42	152.40	4.88 ✓	3.84 ✓	32.91	.96	.34	.15	
152.40	154.38	4.20 ✓	3.90 ✓	26.74	.78	4.20 .17	.20	
154.38	178.00	N/A	N/A	N/A	-	-	-	
178.00	180.29	6.00 ✓	9.40 ✓	112.44	3.28	1.37	.15	
180.29	182.58	8.74 ✓	13.50 ✓	156.32	4.56	1.37	.20	
182.58	211.23	N/A	N/A	N/A	-	-	-	
211.23	213.36	2.40 ✓	2.70 ✓	47.31	1.38	.69	.27	
213.36	214.58	.33 ✓	.54 ✓	24.00	.70	.34	.12	
214.58	221.89	N/A	N/A	N/A	-	-	-	
221.89	224.49	.88 ✓	.66 ✓	31.54	.92	.34	.15	
224.49	227.08	3.38 ✓	5.28 ✓	65.82	1.92	.34	.13	
227.08	249.94	N/A	N/A	N/A	-	-	-	

SPECIAL ORDER BUSINESS FORMS 4

HOLE NO: A-12 LATITUDE: 10997.64 AZIMUTH: 0.00
 HOLE LENGTH: 364.54 DEPARTURE: 7391.02 DIP: -90.00
 ELEVATION: 1323.36

DIP TESTS:	DEPTH	DIP	AZIMUTH
	60.96	-86.30	91.50
	121.92	-83.30	84.20
	182.88	-82.00	97.35
	243.84	-79.15	93.35
	304.80	-79.15	89.30

INTERVAL		ASSAYS						
FROM	TO	PB %	ZN %	AG GM/TON	Ag OZ/TON	AU gm/tonne	Cu	
0.00	227.08	N/A	N/A	N/A	-	-	-	
227.08	230.12	.38✓	.58✓	10.28	.30	.00	.05	
230.12	232.56	2.33✓	7.80✓	43.19	1.26	.34	.04	
232.56	247.19	N/A	N/A	N/A	-	-	-	
247.19	250.24	2.00✓	2.70✓	30.85	.90	.34	.04	
250.24	253.29	3.45✓	3.06✓	44.56	1.30	.34	.07	
253.29	256.34	2.35✓	3.48✓	38.39	1.12	.34	.05	
256.34	260.15	.45✓	.26✓	1.37	.04	.00	.06	
260.15	272.80	N/A	N/A	N/A	-	-	-	
272.80	275.84	1.20✓	2.40✓	21.94	.64	.17	.05	
275.84	278.89	.73✓	1.76✓	13.03	.38	.17	.05	
278.89	281.94	2.18✓	3.90✓	47.99	1.40	.69	.13	
281.94	284.99	1.13✓	1.68✓	18.51	.64	.69	.09	
284.99	288.04	.25✓	.22✓	15.08	.44	.17	.07	
288.04	291.08	1.25✓	1.62✓	30.17	.88	.69	.15	
291.08	294.13	1.00✓	.80✓	28.80	.84	.34	.19	
294.13	297.18	1.03✓	.60✓	26.05	.76	.69	.19	
297.18	300.23	1.45✓	2.40✓	28.11	.82	.69	.13	
300.23	303.28	.48✓	.38✓	4.11	.12	.00	.09	
303.28	306.32	1.00✓	.90✓	32.91	.96	.69	.13	
306.32	309.37	1.45✓	.20✓	52.79	1.54	.69	.21	
309.37	312.42	.80✓	.54✓	24.68	.72	.69	.12	
312.42	315.47	.10✓	.23✓	26.05	.76	.34	.22	
315.47	318.36	.10✓	.19✓	16.45	.48	.69	.15	
318.36	321.41	4.73✓	6.96✓	95.98	2.80	.69	.25	
321.41	354.48	N/A	N/A	N/A	-	-	-	
354.48	355.09	4.43✓	5.10✓	67.53	1.97			
355.09	355.55	5.63✓	6.45✓	67.53	1.97			
355.55	356.16	4.73✓	6.24✓	60.33	1.76			
356.16	357.68	2.78✓	2.70✓	42.51	1.24			
357.68	358.60	5.78✓	8.10✓	72.67	2.12			
358.60	359.91	4.73✓	8.74✓	80.56	2.35			
359.91	361.37	1.40✓	3.54✓	34.28	1.00			
361.37	363.41	2.93✓	8.52✓	58.62	1.71			
363.41	364.54	2.78✓	1.30✓	44.22	1.29			

HOLE NO: A-13
 HOLE LENGTH: 186.23

LATITUDE: 10568.32
 DEPARTURE: 7659.52
 ELEVATION: 1287.69

AZIMUTH: 0.00
 DIP: -90.00

DIP TESTS:	DEPTH	DIP	AZIMUTH
	✓ 48.77	-87.00 ✓	57.20 ✓
	✓ 109.73	-81.30 ✓	88.20 ✓
	✓ 164.59	-77.30 ✓	91.20 ✓

INTERVAL		ASSAYS						
FROM	TO	PB %	ZN %	AG GM/TON	AG OZ/TON	AP gm/tonne	Cu	
0.00	40.69	N/A	N/A	N/A	-	-	-	
40.69	44.35	3.66	1.25 ✓	.62 ✓	26.05	.76	.34	.21
44.35	48.31	3.96	8.10 ✓	8.40 ✓	106.95	3.12	1.37	.16
48.31	52.27	3.96	7.65 ✓	5.52 ✓	92.56	2.70	1.71	.19
52.27	54.86	2.59	N/A	N/A	N/A	-	-	-
54.86	58.98	4.12	5.03 ✓	4.20 ✓	91.87	2.68	.69	.21
58.98	60.05	1.07	1.50 ✓	1.90 ✓	29.48	.86	.17	.15
60.05	61.57	1.52	5.25 ✓	5.40 ✓	71.30	2.08	1.37	.20
61.57	64.16	2.59	1.25 ✓	.16 ✓	33.94	.99	1.02	.08
64.16	66.75	2.59	1.63 ✓	.90 ✓	53.48	1.56	.69	.20
66.75	121.31	N/A	N/A	N/A	N/A	-	-	-
121.31	123.14	1.83	.90 ✓	2.00 ✓	24.68	.72	.34	.03
123.14	125.12	1.98	3.23 ✓	4.74 ✓	67.87	1.98	.69	.15
125.12	130.45	5.53	N/A	N/A	N/A	-	-	-
130.45	136.55	6.10	.80 ✓	1.50 ✓	19.20 } ⑩	.56	.34	.09
136.55	186.23	N/A	N/A	N/A	N/A	-	-	-

SPECIAL MOORE BUSINESS FORMS 4

HOLE NO: A-14
 HOLE LENGTH: 334.70

LATITUDE: 10672.94
 DEPARTURE: 7414.58
 ELEVATION: 1300.78

AZIMUTH: 0.00
 DIP: -90.00

INTERVAL		ASSAYS						
FROM	TO	PB	ZN	AG	AG	Au	Cu	
		%	%	GM/TON	OZ/TON	gm/tonne		
0.00	192.63	N/A	N/A	N/A	-	-	-	
192.63	193.85	1.45✓	1.22✓	21.94	.64	.34	.19	
193.85	266.09	N/A	N/A	N/A	-	-	-	
266.09	272.19	.29✓	.42✓	31.54	.92	.17	.16	
272.19	273.10	.63✓	.69✓	37.02	1.08	.17	.16	
273.10	275.84	6.53✓	6.96✓	91.53	2.67	.69	.30	
275.84	278.89	.55✓	.66✓	12.34	.36	.17	.20	
278.89	281.94	2.00✓	2.76✓	53.48	1.56	.34	.17	
281.94	283.46	.33✓	.46✓	21.94	.64	.34	.15	
283.46	287.12	1.73✓	2.00✓	32.91	.96	.17	.20	
287.12	334.67	N/A	N/A	N/A	-	-	-	

SPRINT LO MOORE BUSINESS FORMS 4

HOLE NO: A-15 LATITUDE: 11294.24 AZIMUTH: 0.00
 DEPARTURE: 7346.49 DIP: -90.00
 ELEVATION: 1327.10

INTERVAL		ASSAYS					
FROM	TO	PB	ZN	AG	AG	Au	Cu
		%	%	GM/TON	OZ/TON	gm/tonne	%
0.00	129.36	N/A	N/A	N/A	-	-	-
129.36	132.25	1.30	1.16	22.62	.66	.17	.16
132.25	138.07	N/A	N/A	N/A	-	-	-
138.07	141.12	3.00	3.00	49.36	1.44	.34	.03
141.12	144.17	6.00	4.02	125.46	3.66	.34	.05
144.17	147.22	3.38	3.48	61.02	1.78	.34	.05
147.22	149.20	5.18	7.44	87.76	2.56	.34	.03
149.20	150.27	3.15	3.48	49.36	1.44	.17	.07
150.27	151.49	5.40	3.18	57.59	1.68	.34	.03
151.49	153.01	3.60	3.54	47.99	1.40	.17	.06
153.01	158.50	N/A	N/A	N/A	-	-	-
158.50	170.69	1.50	2.22	15.08	.44	.17	.03
170.69	173.74	1.98	3.84	34.97	1.02	.34	.03
173.74	176.78	3.60	5.58	48.68	1.42	.34	.04
176.78	179.83	1.83	2.40	29.48	.86	.34	.05
179.83	182.88	2.40	3.42	27.42	.80	.34	.04
182.88	185.93	1.93	2.88	30.17	.88	.34	.04
185.93	189.89	1.40	2.70	24.68	.72	.17	.06
189.89	249.63	N/A	N/A	N/A	-	-	-

MOORE
 SERENITO

HOLE NO: A-16

LATITUDE: 11466.44
 DEPARTURE: 7255.62
 ELEVATION: 1321.10

AZIMUTH: 0.00
 DIP: -90.00

INTERVAL		ASSAYS						
FROM	TO	PB	ZN	AG	AG	Ag	Cu	
		%	%	GM/TON	OZ/TON	gm/tonne	%	
0.00	226.16	196.79	N/A	N/A	N/A	-	-	
226.16	228.90	196.79-203	.68✓	.78✓	22.62	.66	.17	
228.90	231.95	203-211.23	1.19✓	1.72✓	20.57	.60	.34	
231.95	235.00	211.23-231.95	.20✓	.16✓	4.80	.74	.17	
235.00	238.05		.09✓	.01✓	9.60	.28	.69	
238.05	241.10		.05✓	.02✓	9.60	.28	.34	
241.10	244.14		.07✓	.02✓	15.08	.44	.17	
244.14	247.19		.64✓	1.12✓	17.83	.62	.34	
247.19	254.20		N/A	N/A	N/A	-	-	
254.20	257.25		.13✓	.10✓	8.23	.24	.17	
257.25	258.78		N/A	N/A	N/A	-	-	
258.78	261.21		.09✓	.04✓	4.11	.12	.17	
261.21	262.43		N/A	N/A	N/A	-	-	
262.43	265.48		2.30✓	4.98✓	32.91	.96	.34	
265.48	270.66		2.35✓	3.18✓	42.51	1.24	.69	
270.66	271.58		1.58✓	3.24✓	31.54	.92	.69	
271.58	275.23		1.42✓	3.18✓	21.25	.62	.17	
275.23	304.50		N/A	N/A	N/A	-	-	

MOORE SPECIFIC 4

HOLE NO: A-17
 HOLE LENGTH: 283.20

LATITUDE: 10485.40
 DEPARTURE: 7567.43
 ELEVATION: 1284.51

AZIMUTH: 0.00
 DIP: -90.00

INTERVAL		PB %	ASSAYS			AG 02/TON	Au gm/tonne	Cu %
FROM	TO		ZN %	AG GM/TON				
0.00	210.01	N/A	N/A	N/A				
210.01	213.36	3.35	1.98✓	1.54✓	26.74	.78	.17	.45
213.36	216.41	3.05	.34✓	.26✓	6.17	.18	.17	.07
216.41	219.46	3.05	1.83✓	1.40✓	27.42	.80	.34	.25
219.46	221.89	2.43	1.70✓	1.42✓	26.05	.76	.17	.24
221.89	227.08	N/A	N/A	N/A				
227.08	229.51	2.43	1.88✓	1.18✓	31.54	.92	.17	.17
229.51	231.95	N/A	N/A	N/A				
231.95	235.00	3.05	2.00✓	1.58✓	34.28	1.00	.17	.30
235.00	237.13	2.13	.30✓	.30✓	10.97	.32	.34	.22
237.13	238.96	1.83	6.38✓	7.92✓	87.76	2.56	1.02	.23
238.96	239.57	N/A	N/A	N/A				
239.57	241.55	1.98	1.03✓	.65✓	16.45	.48	.17	.10
241.55	242.93	1.38	1.83✓	1.08✓	27.42	.80	.17	.10
242.93	244.45	1.52	3.15✓	5.04✓	45.25	1.32	1.37	.21
244.45	245.97	1.52	.25✓	.16✓	4.80	.14	.17	.17
245.97	247.50	1.53	.50✓	.66✓	6.17	.18	.17	.13
247.50	249.02	1.52	.98✓	1.52✓	17.83	.52	.69	.22
249.02	251.16	2.14	.28✓	.12✓	17.83	.52	.17	.24
251.16	252.07	.91	2.50✓	1.84✓	47.99	1.40	.69	.23
252.07	253.59	1.52	1.85✓	1.26✓	27.42	.80	.17	.28
253.59	255.12	1.53	1.20✓	.51✓	23.31	.68	.34	.30
255.12	256.64	1.52	1.43✓	.66✓	23.31	.68	.34	.33
256.64	258.01	1.37	1.30✓	.61✓	19.88	.58	.17	.25
258.01	283.16	N/A	N/A	N/A				

SPECIFIC MOORE BUSINESS FORMS

HOLE NO: A-18 LATITUDE: 11118.54 AZIMUTH: 0.00
 DEPARTURE: 7171.43 DIP: -90.00
 ELEVATION: 1333.00

DIP TESTS:	DEPTH	DIP	AZIMUTH
	✓30.50	-84.00✓	113.20✓
	✓91.40	-81.00✓	97.20✓
	✓213.40	-78.00✓	136.20✓
	✓274.30	-77.00✓	106.20✓
	329.18 (335.30)	-74.00✓	123.20✓
	✓439.10	-77.00✓	95.20✓

INTERVAL		PB %	ASSAYS			AG OZ/TON	Au gm/tonne	Cu %
FROM	TO		ZN %	AG GM/TON				
0.00	311.20	N/A	N/A	N/A	-	-	-	
311.20	312.72	6.08✓	11.96✓	97.36	2.84	.69	.14	
312.72	313.94	5.10✓	9.53✓	116.55	3.40	1.37	.14	
313.94	315.47	5.48✓	9.24✓	107.98	3.15	1.71	.29	
315.47	316.99	6.45✓	10.11✓	121.69	3.55	1.71	.20	
316.99	317.91	4.43✓	6.48✓	94.61	2.76	1.37	.17	
317.91	319.74	N/A	N/A	N/A	-	-	-	
319.74	320.65	1.85✓	2.28✓	32.22	.94	.69	.08	
320.65	322.17	N/A	N/A	N/A	-	-	-	
322.17	323.70	6.38✓	11.54✓	118.61	3.46	2.06	.11	
323.70	324.92	3.30✓	4.98✓	67.19	1.96	.69	.09	
324.92	326.44	N/A	N/A	N/A	-	-	-	
326.44	327.96	2.78✓	3.84✓	38.39	1.12	.69	.06	
327.96	329.49	1.58✓	3.06✓	30.85	.90	.69	.04	
329.49	331.01	1.50✓	2.58✓	24.00	.70	.69	.05	
331.01	332.84	1.38✓	2.70✓	26.05	.76	.34	.05	
332.84	334.37	1.40✓	3.60✓	45.25	1.32	.17	.03	
334.37	336.19	2.20✓	4.74✓	78.84	2.30	.69	.11	
336.19	337.72	5.93✓	10.92✓	115.18	3.36	1.37	.21	
337.72	339.24	4.73✓	7.32✓	106.95	3.12	.69	.25	
339.24	341.38	.60✓	.87✓	8.23	.24	.17	.04	
341.38	420.50	N/A	N/A	N/A	-	-	-	
420.50	421.90	5.70✓	8.11✓	92.90	2.71	-	-	
421.90	423.40	1.28✓	1.42✓	20.23	.59	-	-	
423.40	425.81	4.73✓	7.56✓	80.56	2.35	-	-	
425.81	448.36	N/A	N/A	N/A	-	-	-	

HOLE NO: A-19 LATITUDE: 10699.70 AZIMUTH: 0.00
HOLE LENGTH: 256.95 DEPARTURE: 7609.33 DIP: -90.00
ELEVATION: 1295.52

DIP TESTS: DEPTH DIP AZIMUTH
60.96 -87.00 118.00
121.92 -83.30 97.30
182.88 -83.00 111.30

INTERVAL		ASSAYS						
FROM	TO	PB %	ZN %	AG GM/TON	Ag O2/TON	Aw gm/tonne	Cu %	
0.00	102.35	N/A	N/A	N/A	-	-	-	
102.35	103.81	1.85	1.92	47.31	1.38	.69	.22	
103.81	105.34	1.18	1.02	10.97	.32	.17	.13	
105.34	108.20	6.68	5.64	109.01	3.18	.69	.11	
108.20	134.72	N/A	N/A	N/A	-	-	-	
134.72	135.94	.05	.17	1.37	.04	.17	.02	
135.94	137.77	2.50	4.02	58.28	1.70	.69	.14	
137.77	139.63	1.15	2.00	31.54	.92	.69	.17	
139.63	142.43	.38	.60	21.94	.64	.34	.34	
142.43	143.65	7.35	9.36	139.86	4.08	1.37	.07	
143.65	147.83	.25	.82	14.40	.42	.69	.18	
147.83	150.27	2.28	1.60	34.28	1.00	.34	.14	
150.27	152.55	4.95	6.96	60.33	1.76	.34	.06	
152.55	154.59	1.33	2.58	10.97	.32	.34	.11	
154.59	155.45	.60	.33	9.60	.28	.34	.09	
155.45	158.92	N/A	N/A	N/A	-	-	-	
158.92	160.75	.88	1.14	9.94	.29	.17	.04	
160.75	161.94	N/A	N/A	N/A	-	-	-	
161.94	163.68	2.25	4.68	58.28	1.70	.69	.11	
163.68	164.59	4.35	6.84	56.22	1.64	.69	.23	
164.59	165.51	7.55	12.72	111.75	3.26	.69	.21	
165.51	166.73	3.15	4.74	50.05	1.46	.69	.11	
166.73	168.25	2.05	3.72	38.39	1.12	.69	.11	
168.25	169.77	2.28	3.90	53.48	1.56	.69	.10	
169.77	171.30	2.50	6.24	52.11	1.52	.69	.16	
171.30	172.82	4.50	9.48	76.79	2.24	.69	.18	
172.82	174.35	4.74	8.64	76.79	2.24	.69	.25	
174.35	175.87	5.78	10.20	109.70	3.20	1.37	.17	
175.87	176.69	3.08	5.76	67.87	1.98	.69	.05	
176.69	177.79	1.85	3.33	46.62	1.36	.34	.03	
177.79	183.37	N/A	N/A	N/A	-	-	-	
183.37	183.89	2.18	5.10	50.73	1.48	1.37	.09	
183.89	194.16	N/A	N/A	N/A	-	-	-	
194.16	197.21	9.15	15.86	137.81	4.02	2.06	.20	
197.21	198.42	1.90	2.88	27.42	.80	.34	.29	
198.42	200.86	5.70	9.49	90.50	2.64	1.37	.26	
200.86	202.51	2.70	3.30	50.73	1.48	1.37	.33	
202.51	205.28	2.93	4.14	55.88	1.63	.69	.29	
205.28	208.18	.08	.37	16.45	.48	.34	.42	
208.18	211.23	.35	1.50	19.20	.56	.69	.26	
211.23	214.27	.14	.35	15.08	.44	.34	.33	
214.27	216.74	.18	.19	10.97	.32	.34	.39	
216.74	219.00	2.85	4.02	33.59	.98	.69	.14	
219.00	220.68	.14	.62	8.23	.24	.34	.44	
220.68	222.20	.07	2.00	8.23	.24	.34	.28	

SPRINT-10 MOORE BUSINESS FORMS 4

015

HOLE NO: A-19

INTERVAL		ASSAYS					
FROM	TO	PB %	ZN %	AG GM/TON	AG OZ/TON	Au gm/tonne	Cu %
222.20	224.94	.10	3.60	9.60	.28	.17	.30
224.94	226.92	.12	3.48	9.60	.28	.17	.43
226.92	227.99	.92	1.40	31.54	.92	.69	.37
227.99	229.51	2.93	2.82	63.76	1.86	.69	.23
229.51	256.95	N/A	N/A	N/A			

SPRUELL MOORE BUSINESS FORMS 4

111

HOLE NO: A-20
HOLE LENGTH: 406.60

LATITUDE: 11038.90
DEPARTURE: 7432.51
ELEVATION: 1321.72

AZIMUTH: 0.00
DIP: -90.00

DIP TESTS:	DEPTH	DIP	AZIMUTH
	30.48 ✓	-89.00 ✓	64.20 ✓
	91.44 ✓	-90.00 ✓	0.00 ✓
	152.40 ✓	-82.00 ✓	65.50 ✓
	225.55 ✓	-84.00 ✓	118.30 ✓
	286.51 ✓	-80.00 ✓	51.00 ✓
365.7	406.60 ✓	-82.00 ✓	67.00 ✓

INTERVAL		PB %	ASSAYS			AG OZ/TON	Au gm/tonne	Cu %
FROM	TO		ZN %	AG GM/TON				
0.00	183.79	N/A	N/A	N/A	-	-	-	
183.79	185.01	.43 ✓	.70 ✓	10.97	.32	.17	.04	
185.01	186.84	2.48 ✓	4.14 ✓	41.82	1.22	.69	.10	
186.84	188.06	N/A	N/A	N/A	-	-	-	
188.06	189.59	1.73 ✓	3.06 ✓	28.11	.82	.69	.04	
189.59	191.11	3.38 ✓	2.46 ✓	43.19	1.26	.69	.08	
191.11	192.63	2.50 ✓	3.54 ✓	56.22	1.64	.34	.04	
192.63	194.16	2.85 ✓	5.52 ✓	35.65	1.04	.34	.06	
194.16	195.68	1.88 ✓	2.88 ✓	27.42	.80	.34	.03	
195.68	197.21	.90 ✓	1.76 ✓	20.57	.60	.34	.04	
197.21	198.73	.88 ✓	1.66 ✓	13.71	.40	.17	.03	
198.73	200.25	.98 ✓	.74 ✓	15.08	.44	.17	.04	
200.25	201.78	.68 ✓	.66 ✓	15.08	.44	.34	.08	
201.78	203.30	1.05 ✓	.66 ✓	15.08	.44	.34	.08	
203.30	204.83	3.15 ✓	4.50 ✓	50.05	1.46	.69	.17	
204.83	206.04	5.25 ✓	8.04 ✓	78.16	2.28	.69	.04	
206.04	210.01	N/A	N/A	N/A	-	-	-	
210.01	211.23	4.35 ✓	6.72 ✓	72.67	2.12	.69	.05	
211.23	212.75	.28 ✓	.27 ✓	17.14	.50	.17	.05	
212.75	214.27	.30 ✓	.48 ✓	5.48	.16	.00	.07	
214.27	215.80	3.23 ✓	4.98 ✓	61.02	1.78	.69	.13	
215.80	217.32	5.10 ✓	9.24 ✓	93.24	2.72	.69	.25	
217.32	218.85	3.38 ✓	7.44 ✓	66.50	1.94	.69	.04	
218.85	220.37	2.85 ✓	6.72 ✓	50.05	1.46	.69	.06	
220.37	221.89	3.15 ✓	7.44 ✓	55.53	1.62	.69	.05	
221.89	223.42	2.43 ✓	5.40 ✓	45.94	1.34	.69	.04	
223.42	224.94	2.00 ✓	3.72 ✓	37.71	1.10	.69	.06	
224.94	226.47	.58 ✓	1.18 ✓	19.20	.56	.34	.06	
226.47	227.99	N/A	N/A	N/A	-	-	-	
227.99	229.51	1.48 ✓	2.58 ✓	37.02	1.08	.34	.05	
229.51	231.34	1.53 ✓	3.24 ✓	28.80	.84	.34	.03	
231.34	237.13	N/A	N/A	N/A	-	-	-	
237.13	238.66	1.38 ✓	2.34 ✓	41.14	1.20	.34	.07	
238.66	240.49	3.15 ✓	5.28 ✓	84.33	2.46	.69	.10	
240.49	247.50	N/A	N/A	N/A	-	-	-	
247.50	249.02	5.55 ✓	7.44 ✓	76.10	2.22	.69	.07	
249.02	250.55	4.50 ✓	3.48 ✓	77.47	2.26	.69	.08	
250.55	251.76	2.15 ✓	3.36 ✓	47.31	1.38	.69	.05	
251.76	256.95	N/A	N/A	N/A	-	-	-	
256.95	258.47	.98 ✓	1.74 ✓	24.68	.72	.34	.05	
258.47	325.01	N/A	N/A	N/A	-	-	-	
325.01	328.00	1.13 ✓	1.04 ✓	16.11	.47	-	-	

HOLE NO: A-20

INTERVAL		ASSAYS				
FROM	TO	PB %	ZN %	AG GM/TON	AG OZ/TON	
328.00	332.51	N/A	N/A	N/A	-	
332.51	333.30	4.43	6.21	77.82	2.27	
333.30	337.69	N/A	N/A	N/A	-	
337.69	338.51	2.08	2.28	53.48	1.56	
338.51	340.19	1.63	2.88	32.22	.94	
340.19	343.20	N/A	N/A	N/A	-	
343.20	344.79	3.38	5.55	67.53	1.97	
344.79	351.01	N/A	N/A	N/A	-	
351.01	352.01	2.78	2.46	45.25	1.32	
352.01	352.99	3.00	2.94	35.31	1.03	
352.99	355.00	.43	.76	5.14	.15	
355.00	356.71	5.03	6.66	78.84	2.30	
356.71	357.20	.20	.30	3.09	.09	
357.20	359.39	.58	.58	22.28	.65	
359.39	360.61	.08	.04	1.03	.03	
360.61	361.61	3.15	6.33	47.31	1.38	
361.61	362.01	.15	.16	2.06	.06	
362.01	362.71	.78	1.30	15.08	.44	
362.71	363.90	4.43	7.94	63.42	1.85	
363.90	364.69	2.20	3.18	40.45	1.18	
364.69	366.00	1.03	1.94	25.37	.74	
366.00	367.01	1.40	2.22	30.17	.88	
367.01	367.99	1.70	2.94	34.28	1.00	
367.99	368.99	1.50	1.60	30.17	.88	
368.99	370.00	.43	.86	19.20	.56	
370.00	371.00	3.75	4.32	64.45	1.88	
371.00	372.19	3.90	4.02	60.33	1.76	
372.19	372.65	1.90	1.84	46.28	1.35	
372.65	374.69	1.75	2.70	32.22	.94	
374.69	406.60	N/A	N/A	N/A	-	

374.3

DIAMOND DRILL LOG MA

STER FILE

HOLE NO: A-21
HOLE LENGTH: 260.91

LATITUDE: 10743.08
DEPARTURE: 7651.38
ELEVATION: 1301.68

AZIMUTH: 0.00
DIP: -90.00

DIP TESTS:	DEPTH	DIP	AZIMUTH
	✓ 60.96	-88.30✓	157.20✓
	✓ 115.82	-85.00✓	117.20✓
	✓ 207.26	-86.00✓	157.20✓

INTERVAL		ASSAYS					
FROM	TO	PB %	ZN %	AG GM/TON	AG OZ/TON	Au gm/tonne	Cu %
0.00	100.10	N/A	N/A	N/A	-	-	-
100.10	101.07	.03✓	.10✓	.00	TR	.00	.02
101.07	103.51	5.78✓	11.35✓	79.53	2.32	.69	.08
103.51	104.30	.10✓	.30✓	.00	TR	.00	.02
104.30	107.14	8.25✓	14.83✓	149.46	4.36	.69	.15
107.14	109.42	2.23✓	4.26✓	32.22	.94	.17	.03
109.42	112.35	4.43✓	8.76✓	56.22	1.64	.34	.06
112.35	113.69	3.75✓	1.44✓	39.76	1.16	.34	.06
113.69	115.21	4.20✓	1.50✓	45.94	1.34	.34	.05
115.21	117.35	.68✓	1.74✓	9.60	.28	.17	.08
117.35	119.09	.64✓	1.66✓	9.60	.28	.17	.08
119.09	121.10	.70✓	1.34✓	10.97	.32	.17	.10
121.10	123.20	.63✓	1.14✓	10.28	.30	.17	.08
123.20	132.28	N/A	N/A	N/A	-	-	-
132.28	133.81	.03✓	.05✓	.00	TR	.17	.02
133.81	167.03	N/A	N/A	N/A	-	-	-
167.03	168.55	.08✓	.33✓	.00	TR	.00	.02
168.55	171.39	N/A	N/A	N/A	-	-	-
171.39	172.36	1.60✓	3.24✓	23.31	.68	.17	.04
172.36	179.83	N/A	N/A	N/A	-	-	-
179.83	181.20	.08✓	.10✓	8.91	.26	.00	.03
181.20	183.34	2.43✓	4.74✓	42.51	1.24	.34	.12
183.34	185.32	3.08✓	5.04✓	47.99	1.40	.34	.09
185.32	186.84	2.50✓	4.20✓	52.11	1.52	.34	.09
186.84	189.89	4.43✓	8.76✓	71.30	2.08	.69	.12
189.89	192.94	4.28✓	9.12✓	76.79	2.24	.69	.04
192.94	194.46	5.03✓	9.36✓	83.64	2.44	.69	.17
194.46	195.99	6.83✓	11.50✓	128.89	3.76	1.37	.17
195.99	197.51	2.25✓	4.26✓	51.42	1.50	.69	.15
197.51	200.25	5.18✓	9.00✓	45.25	1.32	.34	.12
200.25	201.78	.15✓	.23✓	5.48	.16	.34	.11
201.78	203.39	.42✓	.74✓	6.86	.20	.17	.07
203.39	210.13	N/A	N/A	N/A	-	-	-
210.13	212.42	.98✓	1.58✓	10.97	.32	.34	.08
212.42	214.55	.18✓	.51✓	16.45	.48	.34	.12
214.55	216.87	.34✓	.29✓	8.23	.24	.17	.10
216.87	218.60	.74✓	1.10✓	5.48	.16	.34	.06
218.60	221.04	1.53✓	2.22✓	20.57	.60	.34	.06
221.04	223.91	.23✓	.33✓	9.60	.28	.34	.13
223.91	226.56	1.35✓	1.19✓	26.05	.76	.34	.16
226.56	227.99	.15✓	.46✓	9.60	.28	.34	.22
227.99	231.04	.10✓	.14✓	10.97	.32	.34	.18
231.04	232.56	.18✓	.25✓	8.23	.24	.17	.18
232.56	234.09	.89✓	1.08✓	23.31	.68	.34	.10
234.09	236.22	1.25✓	1.54✓	24.68	.72	.34	.12

SHEET 10 MORE BUSINESS FORMS 4

HOLE NO: A-21

INTERVAL		ASSAYS						
FROM	TO	PB %	ZN %	AG GM/TON	AG OZ/TON	Au gm/tonne	Cu %	
236.22	237.44	.54 ✓	.78 ✓	9.60	.28	34	.12	
237.44	240.49	.17 ✓	.28 ✓	5.48	.16	34	.30	
240.49	243.54	.08 ✓	.19 ✓	6.17	.18	34	.17	
243.54	246.28	.08 ✓	.56 ✓	9.60	.28	17	.25	
246.28	248.35	1.93 ✓	2.64 ✓	38.39	1.12	34	.32	
248.35	260.91	N/A	N/A	N/A	—			

SPECIALTY MOORE BUSINESS FORMS 4

HOLE NO: A-22
 HOLE LENGTH: 384.66

LATITUDE: 10949.58
 DEPARTURE: 7345.91
 ELEVATION: 1322.15

AZIMUTH: 0.00
 DIP: -90.00

DIP TESTS:	DEPTH	DIP	AZIMUTH
	✓60.96	-83.30✓	119.20 ✓
	✓121.92	-81.00✓	103.20 ✓
	✓182.88	-81.00✓	103.20 ✓
	✓243.84	-76.30✓	102.20 ✓
	✓353.57	-80.00✓	154.20 ✓

INTERVAL		ASSAYS						
FROM	TO	PB %	ZN %	AG GM/TON	AG OZ/TON	Au gm/tonne	Cu %	
0.00	154.23	N/A	N/A	N/A	-	-	-	
154.23	154.72	1.45✓	1.58✓	23.31	.68	.34	.44	
154.72	174.19	N/A	N/A	N/A	-	-	-	
174.19	175.72	.75✓	.50✓	5.48	.16	.17	.18	
175.72	178.70	.23✓	.18✓	.69	.02	.00	.07	
178.70	180.41	N/A	N/A	N/A	-	-	-	
180.41	180.99	.78✓	.78✓	10.97	.32	.34	.27	
180.99	183.25	5.03✓	5.52✓	68.56	2.00	.69	.13	
183.25	184.77	6.00✓	6.84✓	105.93	3.09	.69	.16	
184.77	186.90	.78✓	1.06✓	9.94	.29	.17	.13	
186.90	188.70	.85✓	2.40✓	30.17	.88	.17	.24	
188.70	229.88	N/A	N/A	N/A	-	-	-	
229.88	231.04	4.35✓	8.50✓	58.96	1.72	.69	.12	
231.04	232.11	6.83✓	8.40✓	133.01	3.88	1.37	.27	
232.11	233.78	3.23✓	4.44✓	50.73	1.48	.69	.15	
233.78	236.83	5.33✓	8.88✓	78.16	2.28	.69	.09	
236.83	239.88	2.35✓	5.16✓	47.99	1.40	.69	.07	
239.88	242.62	2.08✓	4.56✓	58.96	1.72	.69	.06	
242.62	243.38	1.93✓	3.06✓	23.31	.68	.34	.08	
243.38	245.82	.23✓	.43✓	5.48	.16	.17	.08	
245.82	247.01	.63✓	.25✓	20.57	.60	.17	.12	
247.01	250.00	3.83✓	6.96✓	52.11	1.52	.34	.10	
250.00	251.31	.69✓	1.40✓	16.45	.48	.34	.28	
251.31	252.56	2.08✓	2.00✓	45.25	1.32	.69	.31	
252.56	254.48	4.35✓	8.16✓	62.39	1.82	.69	.12	
254.48	257.43	4.35✓	7.68✓	66.50	1.94	.69	.21	
257.43	270.54	N/A	N/A	N/A	-	-	-	
270.54	271.03	6.68✓	11.45✓	152.20	4.44	.69	.08	
271.03	273.71	N/A	N/A	N/A	-	-	-	
273.71	274.44	.08✓	.10✓	6.86	.20	.00	.02	
274.44	275.33	1.58✓	3.00✓	27.42	.80	.69	.04	
275.33	276.76	6.60✓	12.67✓	94.61	2.76	.69	.08	
276.76	278.83	6.00✓	11.92✓	127.52	3.72	.69	.15	
278.83	279.81	.05✓	.06✓	1.37	.04	.17	.03	
279.81	342.93	N/A	N/A	N/A	-	-	-	
342.93	344.94	4.35✓	7.20✓	80.90	2.36	.69	.10	
344.94	345.40	6.08✓	10.65✓	98.73	2.88	.69	.09	
345.40	347.47	3.53✓	6.36✓	43.88	1.28	.69	.09	
347.47	349.18	3.53✓	6.60✓	49.36	1.44	.69	.04	
349.18	352.23	4.88✓	7.80✓	100.10	2.92	.69	.10	
352.23	354.85	5.18✓	8.76✓	88.79	2.59			
354.85	355.49	.50✓	.77✓	6.17	.18			
355.49	356.34	4.58✓	7.80✓	87.76	2.56			

Cost ca.

SPECIAL MOORE BUSINESS FORMS 4

HOLE NO: A-23
HOLE LENGTH: 306.02

LATITUDE: 10616.47
DEPARTURE: 7697.84
ELEVATION: 1288.52

AZIMUTH: 0.00
DIP: -90.00

DIP TESTS: DEPTH DIP AZIMUTH
 ✓51.81 -88.00° 34.42 283.0°
 ✓91.44 -89.00° 112.20 133.0°
 ✓146.30 -88.00° 102.20 113.0°

INTERVAL		ASSAYS					
FROM	TO	PB %	ZN %	AG GM/TON	AG GM/TON	AG GM/TON	AG GM/TON
0.00	78.03	N/A	N/A	N/A			
78.03	78.94	.91	12.20	23.40	177.57	5.18	
78.94	80.16	1.22	11.20	21.10	176.54	5.15	
80.16	81.08	.92	7.35	12.41	105.93	3.09	①
81.08	83.06	1.98	5.40	10.50	82.61	2.41	
83.06	83.97	.91	.48	.51	16.11	.47	
83.97	85.65	1.68	4.28	7.08	58.62	1.71	
85.65	87.33	1.68	1.45	1.16	17.14	.60	
87.33	89.00	1.67	.70	1.48	10.97	.32	
89.00	92.66	3.66	.98	1.60	14.05	.41	②
92.66	95.71	3.05	.43	.87	9.26	.27	
95.71	99.06	3.35	.75	1.12	12.00	.35	
99.06	100.89	1.83	2.85	4.86	40.45	1.18	
100.89	101.44	.55	5.55	12.10	85.70	2.50	
101.44	102.72	1.26	4.88	10.80	100.78	2.94	
102.72	105.77	3.05	4.50	9.00	70.62	2.06	③
105.77	108.66	2.89	2.93	8.16	50.39	1.47	
108.66	110.95		N/A	N/A	N/A	-	
110.95	112.56	1.61	4.50	9.48	75.76	2.21	
112.56	114.91	2.35	N/A	N/A	N/A	-	
114.91	117.96	3.05	9.00	19.50	157.35	4.59	④
117.96	121.01	3.05	8.10	19.61	126.15	3.68	
121.01	124.05	3.04	9.60	19.00	151.17	4.41	⑤
124.05	127.41	3.36	5.73	10.54	91.87	2.68	
127.41	129.84	2.43	.37	1.32	13.03	.38	
129.84	131.67	1.83	.28	1.26	14.05	.41	⑥
131.67	133.81	2.19	2.93	6.12	37.37	1.09	
133.81	135.94	2.13	6.90	14.59	109.01	3.18	⑦
135.94	137.77	1.83	8.25	15.71	121.01	3.53	
137.77	140.82	3.05	3.23	3.78	36.34	1.06	
140.82	143.87	3.05	.55	.76	13.03	.38	
143.87	146.91	3.04	.89	2.00	16.11	.47	
146.91	149.96	3.05	.44	1.04	12.00	.35	⑧
149.96	153.01	3.05	.20	1.38	9.26	.27	
153.01	155.14	2.13	.17	1.04	6.17	.18	
155.14	158.19	3.05	.29	.60	12.00	.35	
158.19	161.24	3.05	.17	.67	14.05	.41	
161.24	162.76	1.52	.27	.79	7.20	.21	
162.76	163.98	1.22	3.83	4.56	65.47	1.91	⑨
163.98	165.81	1.83	1.45	.70	29.14	.85	
165.81	167.94	2.13	.14	.37	8.91	.26	
167.94	170.02	2.08	.08	.78	12.00	.35	
170.02	173.13	3.11	.05	.29	5.14	.15	
173.13	173.74	.63	.22	.65	8.23	.24	
173.74	176.17	2.43	2.18	2.94	35.31	1.03	

266-272.5

FROM	TO	Pb %	Zn %	Ag g/Ton	Au gm/tonne	Cu %
206.65	209.25 ⁰²	1.80	2.40	.66	.69	.09
209.25	210.31	.80	1.44	.59	.34	.15
210.31	213.36	2.33	3.66	1.02	.69	.10
213.36	216.41	.44	.58	.20	.34	.13
216.41	219.46	1.85	2.52	.75	.34	.10
219.46	220.98	.10	1.32	.24	.34	.17
220.98	222.50	.70	1.16	.54	.69	.31
222.50	224.03	7.35	11.61	3.44	1.37	.13
224.03	225.55	4.95	7.20	2.84	1.37	.22
225.55	227.08	5.80	7.63	3.16	1.37	.23
227.08	228.60	5.10	9.52	2.56	1.37	.31
228.60	230.43	2.50	4.20	1.18	.69	.13
230.43	233.78	N/A	N/A	N/A	N/A	N/A
233.78	236.34	3.00	6.72	1.82	.69	.06
236.34	237.44	N/A	N/A	N/A	N/A	N/A
237.44	238.66	1.73	3.12	1.02	.69	.05
238.66	239.27	N/A	N/A	N/A	N/A	N/A
239.27	240.06	5.25	13.80	2.80	.69	.18
240.06	244.45	N/A	N/A	N/A	N/A	N/A
244.45	246.43	5.25	7.44	2.40	1.37	.20
246.43	248.41	3.75	5.10	2.08	.69	.19

A-10

023

HOLE NO: A-23

INTERVAL		ASSAYS					AG
FROM	TO	PB %	ZN %	AG GM/TON		02/TON	
176.17	221.89	N/A	N/A	N/A		-	
221.89	224.33	2.44 .03 ✓	.03 ✓	2.06		.06	
224.33	235.46	N/A	N/A	N/A		-	
235.46	237.59	2.13 4.80 ✓	6.48 ✓	60.33		1.76	
237.59	239.42	1.83 N/A	N/A	N/A		-	
239.42	242.01	2.59 3.38 ✓	3.48 ✓	54.51		1.59	
242.01	243.54	1.44 2.80 ✓	1.18 ✓	34.28		1.00	
243.54	245.27	1.73 2.78 ✓	3.66 ✓	46.28		1.35	
245.27	246.89	1.62 .32 ✓	.76 ✓	5.14		.15	
246.89	262.74	N/A	N/A	N/A		-	
262.74	263.96	1.22 .73 ✓	.98 ✓	12.00		.35	
263.96	265.18	1.22 .85 ✓	.58 ✓	18.17		.53	
265.18	267.00	1.82 .50 ✓	.60 ✓	10.97		.32	
267.00	275.69	N/A	N/A	N/A		-	
275.69	277.06	1.37 1.43 ✓	1.08 ✓	21.25		.62	
277.06	278.43	1.37 N/A	N/A	N/A		-	
278.43	280.42	1.99 .82 ✓	.82 ✓	14.05		.41	
280.42	306.02	N/A	N/A	N/A		-	

2.20

72

SPECIAL TO MOORE BUSINESS FORMS 4

HOLE NO: A-24 LATITUDE: 10865.37 AZIMUTH: 0.00
 HOLE LENGTH: 356.31 DEPARTURE: 7432.51 DIP: -90.00
 ELEVATION: 1314.47

DIP TESTS:	DEPTH	DIP	AZIMUTH
	✓60.96	-85.00✓	52.20 ✓
	✓121.92	-84.30✓	82.20 ✓
	✓182.88	-82.00✓	64.40 ✓
	✓256.03	-87.00✓	82.20 ✓

INTERVAL		ASSAYS			AG
FROM	TO	PB	ZN	AG	AG
		%	%	GM/TON	02/ TON
0.00	139.81	N/A	N/A	N/A	
139.81	142.83	6.15✓	5.40✓	90.84	2.65
142.83	143.41	1.25✓	.74✓	20.23	.59
143.41	144.75	.07✓	.08✓	.00	TR
144.75	146.03	5.55✓	3.54✓	86.73	2.53
146.03	147.37	.18	.04✓	4.11	.12
147.37	150.45	7.20✓	6.12✓	97.70	2.85
150.45	150.88	.65✓	.68✓	9.26	.27
150.88	177.24	N/A	N/A	N/A	
177.24	177.70	.78✓	1.50✓	3.09	.09
177.70	178.40	.08✓	.11✓	2.06	.06
178.40	179.22	7.20✓	12.30✓	122.04	3.56
179.22	180.14	3.53✓	4.86✓	60.33	1.76
180.14	181.97	2.13✓	3.72✓	35.31	1.03
181.97	185.01	7.20✓	10.20✓	102.84	3.00
185.01	187.27	3.83✓	7.56✓	75.76	2.21
187.27	188.37	2.40✓	4.50✓	37.37	1.09
188.37	189.13	.85✓	1.74✓	16.11	.47
189.13	191.87	.19✓	.50✓	5.14	.15
191.87	194.16	8.25✓	14.63✓	111.07	3.24
194.16	196.08	4.13✓	7.92✓	64.45	1.88
196.08	197.60	3.83✓	6.96✓	60.33	1.76
197.60	199.40	2.35✓	5.64✓	37.37	1.09
199.40	201.05	2.85✓	4.92✓	39.42	1.15
201.05	203.15	5.70✓	6.24✓	60.33	1.76
203.15	204.12	4.05✓	2.76✓	57.59	1.68
204.12	205.13	.72✓	.63✓	14.05	.41
205.13	208.12	.73✓	.36✓	15.08	.44
208.12	210.59	.62✓	.82✓	12.00	.35
210.59	213.02	.30✓	.65✓	7.20	.21
213.02	215.40	1.95✓	3.42✓	28.45	.83
215.40	216.71	.49✓	.77✓	7.20	.21
216.71	218.42	3.30✓	6.12✓	42.51	1.24
218.42	219.36	1.65✓	2.34✓	15.08	.44
219.36	221.28	2.05✓	3.18✓	31.19	.91
221.28	223.11	2.50✓	3.54✓	32.22	.94
223.11	223.42	2.50✓	3.24✓	42.51	1.24
223.42	224.64	.72✓	.98✓	15.08	.44
224.64	226.16	.03✓	1.06✓	1.03	.03
226.16	226.62	.25✓	.41✓	3.09	.09
226.62	227.99	.37	1.60✓	9.94	.29
227.99	228.90	2.15✓	3.90✓	60.33	1.76
228.90	229.51	2.50✓	4.92✓	70.62	2.06
229.51	229.82	.08	.34✓	3.09	.09

HOLE NO: A-26
HOLE LENGTH: 273.41

LATITUDE: 10530.88
DEPARTURE: 7785.18
ELEVATION: 1287.67

AZIMUTH: 0.00
DIP: -90.00

DIP TESTS:	DEPTH	DIP	AZIMUTH
	121.92 ✓	-89.00 ✓	71.00 ✓
	207.26 ✓	-87.00 ✓	80.00 ✓
	273.41 ✓	-88.00 ✓	91.00 ✓
	243.8		

INTERVAL		ASSAYS				
FROM	TO	PB %	ZN %	AG GM/TON	AG OZ/TON	
0.00	46.63	N/A	N/A	N/A		
46.63	49.68	1.55 ✓	3.84 ✓	25.37	.74	
49.68	51.51	2.30 ✓	5.16 ✓	28.45	.83	
51.51	55.78	N/A	N/A	N/A		
55.78	57.82	2.00 ✓	3.24 ✓	20.23	.59	
57.82	59.44	4.13 ✓	9.96 ✓	100.78	2.94	
59.44	61.42	5.55 ✓	13.20 ✓	103.87	3.03	
61.42	62.06	N/A	N/A	N/A		
62.06	63.70	7.80 ✓	17.55 ✓	130.95	3.82	
63.70	65.23	6.30 ✓	14.45 ✓	102.84	3.00	
65.23	68.03	7.35 ✓	15.54 ✓	116.89	3.41	
68.03	69.65	3.30 ✓	11.67 ✓	51.42	1.50	
69.65	70.41	N/A	N/A	N/A		
70.41	71.17	3.15 ✓	6.24 ✓	51.42	1.50	
71.17	72.54	.53 ✓	1.44 ✓	9.94	.29	
72.54	73.67	3.68 ✓	8.04 ✓	63.42	1.85	
73.67	74.46	6.60 ✓	16.30 ✓	105.93	3.09	
74.46	74.98	.69 ✓	1.00 ✓	10.97	.32	
74.98	75.59	N/A	N/A	N/A		
75.59	76.05	6.90 ✓	14.22 ✓	121.01	3.53	
76.05	77.57	N/A	N/A	N/A		
77.57	80.62	6.53 ✓	13.92 ✓	111.07	3.24	
80.62	81.69	8.40 ✓	14.10 ✓	142.26	4.15	
81.69	82.60	9.30 ✓	19.50 ✓	213.91	6.24	
82.60	85.65	8.25 ✓	15.80 ✓	130.95	3.82	
85.65	88.09	9.60 ✓	18.90 ✓	171.40	5.00	
88.09	91.14	5.85 ✓	7.44 ✓	105.93	3.09	
91.14	94.18	6.15 ✓	9.00 ✓	105.93	3.09	
94.18	96.16	6.23 ✓	7.56 ✓	83.64	2.44	
96.16	98.33	1.58 ✓	1.06 ✓	22.28	.65	
98.33	100.58	3.08 ✓	3.72 ✓	35.31	1.03	
100.58	103.27	.32 ✓	.74 ✓	6.17	.18	
103.27	105.00	1.38 ✓	1.35 ✓	17.14	.50	
105.00	106.22	7.05 ✓	8.04 ✓	97.70	2.85	
106.22	108.97	1.35 ✓	3.00 ✓	20.23	.59	
108.97	112.01	1.28 ✓	1.35 ✓	24.34	.71	
112.01	115.06	.18 ✓	1.10 ✓	30.17	.88	
115.06	118.11	.14 ✓	.92 ✓	10.97	.32	
118.11	121.16	.07 ✓	.65 ✓	6.17	.18	
121.16	124.21	.35 ✓	1.74 ✓	14.05	.41	
124.21	127.25	.01 ✓	1.34 ✓	5.14	.15	
127.25	128.47	.18 ✓	1.04 ✓	7.20	.21	
128.47	129.54	3.98 ✓	4.20 ✓	64.45	1.88	
129.54	131.83	1.50 ✓	1.43 ✓	28.45	.83	
131.83	134.72	2.33 ✓	2.40 ✓	41.48	1.21	

K

SPECIFIC MODEL BUSINESS FORM 4

HOLE NO: A-26

INTERVAL		ASSAYS			
FROM	TO	PB %	ZN %	AG GM/TON	AG OZ/TON
134.72	137.77	4.73 ✓	4.02 ✓	65.47	1.91
137.77	140.82	3.08 ✓	2.88 ✓	48.33	1.41
140.82	143.87	1.33 ✓	2.28 ✓	27.42	.80
143.87	144.78	3.00 ✓	3.54 ✓	46.28	1.35
144.78	147.13	2.08 ✓	3.48 ✓	35.31	1.03
147.13	181.51	N/A	N/A	N/A	-
181.51	183.31	3.38 ✓	3.60 ✓	37.37	1.09
183.31	208.67	N/A	N/A	N/A	-
208.67	209.55	4.95 ✓	6.84 ✓	80.56	2.35
209.55	210.37	.47 ✓	.86 ✓	15.08	.44
210.37	211.74	4.13 ✓	5.52 ✓	73.70	2.15
211.74	273.41	N/A	N/A	N/A	-

HOLE NO: A-27
 HOLE LENGTH: 349.61

LATITUDE: 10911.85
 DEPARTURE: 7477.25
 ELEVATION: 1314.27

AZIMUTH: 0.00
 DIP: -90.00

DIP TESTS:	DEPTH	DIP	AZIMUTH
	✓60.96	-86.51✓	117.20✓
	✓121.92	-83.00✓	82.50✓
	✓182.88	-84.00✓	82.20✓
	✓243.84	-85.00✓	132.20✓
	✓304.80	-82.00✓	222.20✓

INTERVAL		ASSAYS			
FROM	TO	PB %	ZN %	AG GM/TON	AG OZ/TON
0.00	160.26	N/A	N/A	N/A	-
160.26	160.93	1.90✓	2.82✓	35.31	1.03
160.93	162.00	2.50✓	4.50✓	48.33	1.41
162.00	165.20	2.23✓	4.92	45.25	1.32
165.20	168.25	2.78✓	4.92✓	47.31	1.38
168.25	169.77	3.45✓	5.64✓	82.61	2.41
169.77	172.06	1.63✓	3.24✓	26.40	.77
172.06	174.96	.93✓	.77✓	10.97	.32
174.96	177.70	1.14✓	.89✓	16.11	.47
177.70	180.75	2.00✓	2.10✓	26.40	.77
180.75	183.34	3.08✓	.88✓	33.25	.97
183.34	184.65	2.78✓	3.60✓	32.22	.94
184.65	185.53	.73✓	.94✓	12.00	.35
185.53	187.76	.42✓	.54✓	9.94	.29
187.76	190.80	.54✓	.86✓	9.94	.29
190.80	193.85	.63✓	1.48✓	9.94	.29
193.85	195.22	.43✓	1.14✓	6.17	.18
195.22	196.90	1.24✓	1.96✓	23.31	.68
196.90	199.19	1.73✓	1.98✓	30.17	.88
199.19	200.65	4.05✓	10.20✓	66.50	1.94
200.65	203.70	.88✓	1.80✓	14.05	.41
203.70	205.50	N/A	N/A	N/A	-
205.50	206.50	.99✓	2.40✓	5.14	.15
206.50	207.78	1.33✓	2.88✓	20.23	.59
207.78	209.09	N/A	N/A	N/A	-
209.09	212.14	2.35✓	3.86✓	35.31	1.03
212.14	215.19	2.40✓	2.28✓	35.31	1.03
215.19	217.32	4.13✓	3.18✓	55.53	1.62
217.32	219.15	5.10✓	3.24✓	68.56	2.00
219.15	220.98	5.25✓	6.48	75.76	2.21
220.98	223.02	7.05✓	10.98✓	118.95	3.47
223.02	225.25	2.50✓	3.24	44.22	1.29
225.25	228.30	1.05✓	2.22	18.17	.53
228.30	231.34	2.70✓	3.42✓	37.37	1.09
231.34	234.39	1.23✓	1.06✓	18.17	.53
234.39	258.17	N/A	N/A	N/A	-
258.17	259.69	.40✓	.60✓	8.23	.24
259.69	262.74	1.08✓	1.30✓	22.28	.65
262.74	265.79	2.20✓	1.72✓	28.45	.83
265.79	268.83	1.83✓	2.40✓	30.17	.88
268.83	271.88	2.23✓	2.34✓	31.19	.91
271.88	274.93	2.18✓	2.22✓	27.42	.80
274.93	277.37	N/A	N/A	N/A	-

SPECIAL TO MOORE BUSINESS FORMS

029

HOLE NO: A-27

INTERVAL		ASSAYS				
FROM	TO	PB %	ZN %	AG GM/TON	AG OZ/TON	
277.37	278.89	1.33 ✓	1.20 ✓	17.14	.50	
278.89	280.42	2.33 ✓	3.84 ✓	33.25	.97	
280.42	281.94	3.00 ✓	4.38 ✓	39.42	1.15	
281.94	284.99	.78 ✓	1.38 ✓	15.08	.44	
284.99	287.52	1.15 ✓	1.94 ✓	25.37	.74	
287.52	325.68	N/A	N/A	N/A	-	
325.68	326.29	.07 ✓	.16 ✓	1.03	.03	
326.29	327.36	3.90 ✓	6.96 ✓	60.33	1.76	
327.36	327.72	.18 ✓	.38 ✓	5.14	.13	
327.72	330.19	1.73 ✓	2.46 ✓	26.40	.77	
330.19	332.08	.49 ✓	.57 ✓	7.20	.21	
332.08	335.13	3.45 ✓	7.08 ✓	62.39	1.82	
335.13	338.18	4.73 ✓	8.88 ✓	70.62	2.06	
338.18	340.00	1.93 ✓	3.00 ✓	31.19	.91	
340.00	342.75	2.18 ✓	3.30 ✓	38.39	1.12	
342.75	344.12	.17 ✓	.45 ✓	13.03	.38	
344.12	345.64	3.15 ✓	4.62 ✓	50.39	1.47	
345.64	349.61	N/A	N/A	N/A	-	

SHEDDLE TO MOORE BUSINESS FORMS 4

HOLE NO: A-28
HOLE LENGTH: 280.72

LATITUDE: 10486.81
DEPARTURE: 7741.81
ELEVATION: 1284.65

AZIMUTH: 0.00
DIP: -90.00

DIP TESTS: DEPTH DIP AZIMUTH
 ✓ 85.34 -85.30 ✓ 50.20 ✓ 05.0
 ✓ 115.82 -86.00 ✓ 97.20 ✓ 49.0
 ✓ 195.07 -76.00 ✓ 84.20 ✓
 243.8 (274.32) -75.00 ✓ 117.20 74.0

INTERVAL		PB	ASSAYS			AG
FROM	TO		ZN	AG	OR/TOM	
		%	%	GM/TON		
0.00	50.60	N/A	N/A	N/A	-	-
50.60	51.05	.84 ✓	.84 ✓	15.08	.44	-
51.05	85.13	N/A	N/A	N/A	-	-
85.13	85.65	.79 ✓	.80 ✓	14.05	.41	-
85.65	88.09	6.68 ✓	11.04 ✓	115.87	3.38	-
88.09	89.37	2.08 ✓	1.38 ✓	32.22	.94	-
89.37	90.89	N/A	N/A	N/A	-	-
90.89	91.41	3.68 ✓	10.20 ✓	115.87	3.38	-
91.41	91.59	N/A	N/A	N/A	-	-
91.59	92.60	6.68 ✓	10.97 ✓	126.15	3.68	-
92.60	124.05	N/A	N/A	N/A	-	-
124.05	125.88	1.28 ✓	1.80 ✓	20.23	.59	-
125.88	128.32	.85 ✓	1.12 ✓	18.17	.53	-
128.32	131.37	.48 ✓	.62 ✓	7.20	.21	-
131.37	133.81	.77 ✓	.65 ✓	19.20 20.23	.59	-
133.81	193.55	N/A	N/A	N/A	-	-
193.55	195.47	.53 ✓	.66 ✓	9.26	.27	-
195.47	213.97	N/A	N/A	N/A	-	-
213.97	214.30	.05 ✓	.03 ✓	5.14	.15	-
214.30	215.62	.93 ✓	.77 ✓	16.11	.47	-
215.62	217.08	3.53 ✓	2.52 ✓	46.28	1.35	-
217.08	217.66	.83 ✓	.59 ✓	25.37	.74	-
217.66	219.24	1.28 ✓	1.26 ✓	28.45	.83	-
219.24	221.59	3.75 ✓	3.00 ✓	52.45	1.53	-
221.59	224.64	1.50 ✓	.82 ✓	30.17	.88	-
224.64	227.69	2.85 ✓	3.24 ✓	44.56	1.30	-
227.69	228.30	.49 ✓	.91 ✓	14.05	.41	-
228.30	242.62	N/A	N/A	N/A	-	-
242.62	243.99	.12 ✓	.09 ✓	5.14	.15	-
243.99	248.72	N/A	N/A	N/A	-	-
248.72	250.24	.05 ✓	.08 ✓	1.03	.03	-
250.24	252.83	N/A	N/A	N/A	-	-
252.83	255.42	1.02 ✓	1.08 ✓	18.17	.53	-
255.42	260.15	N/A	N/A	N/A	-	-
260.15	261.67	.75 ✓	.60 ✓	20.23	.59	-
261.67	280.72	N/A	N/A	N/A	-	-

SPECIAL TO MOORE BUSINESS FORMS 4

HOLE NO: A-29
HOLE LENGTH: 465.73

LATITUDE: 11498.39
DEPARTURE: 6857.36
ELEVATION: 1317.20

AZIMUTH: 0.00
DIP: -90.00

INTERVAL		ASSAYS				
FROM	TO	PB	ZN	AG	AG	
		%	%	GM/TON	OR/TON	
0.00	368.50	N/A	N/A	N/A	-	
368.50	371.25	.93 ✓	2.22 ✓	9.94	.29	
371.25	374.29	1.23 ✓	2.22 ✓	18.16	.53	
374.29	375.33	.65 ✓	1.28 ✓	7.20	.21	
375.33	377.65	1.65 ✓	2.58 ✓	14.05	.41	
377.65	379.17	.80 ✓	1.42 ✓	9.94	.29	
379.17	382.22	1.18 ✓	1.46 ✓	15.08	.44	
382.22	385.75	N/A	N/A	N/A	-	
385.75	388.62	1.44 ✓	2.40 ✓	24.34	.71	
388.62	391.67	1.23 ✓	2.00 ✓	16.11	.47	
391.67	393.95	2.00 ✓	4.00	17.14	.50	4.02
393.95	403.65	N/A	N/A	N/A	-	
403.65	405.08	1.28 ✓	2.94 ✓	22.28	.65	
405.08	406.60	N/A	N/A	N/A	-	
406.60	407.97	1.80 ✓	4.20 ✓	37.37	1.09	
407.97	408.43	2.28 ✓	4.92 ✓	44.22	1.29	
408.43	409.96	2.50 ✓	4.80 ✓	42.51	1.24	
409.96	411.48	1.93 ✓	4.20 ✓	32.22	.94	
411.48	413.31	2.48 ✓	1.36 ✓	30.17	.88	
413.31	414.53	2.33 ✓	5.10 ✓	30.17	.88	
414.53	436.05	N/A	N/A	N/A	-	
436.05	436.84	.22 ✓	.41 ✓	5.14	.15	
436.84	438.61	3.68 ✓	16.67 ✓	80.56	2.35	
438.61	439.06	1.35 ✓	5.40 ✓	21.25	.62	
439.06	439.83	1.30 ✓	3.84 ✓	22.28	.65	
439.83	441.96	N/A	N/A	N/A	-	
441.96	442.94	.58 ✓	1.60 ✓	12.00	.35	
442.94	465.73	N/A	N/A	N/A	-	

SPECIFIC MOORE BUSINESS FORMS 4

HOLE NO: A-30
 HOLE LENGTH: 389.53

LATITUDE: 10840.94
 DEPARTURE: 7578.39
 ELEVATION: 1313.87

AZIMUTH: 0.00
 DIP: -90.00

DIP TESTS:	DEPTH	DIP	AZIMUTH
	✓60.96	-81.30✓	122.20✓
	✓121.92	-76.00✓	110.20✓
	✓182.88	-82.00✓	96.20✓
	✓262.13	-84.00✓	122.20✓

INTERVAL		ASSAYS			AG
FROM	TO	PB	ZN	AG	AG
		%	%	GM/TON	02/TON
0.00	144.54	N/A	N/A	N/A	-
144.54	145.39	8.70✓	17.10✓	148.09	4.32
145.39	146.30	.23✓	.42✓	5.14	.15
146.30	148.44	2.20✓	5.16✓	37.37	1.09
148.44	150.57	.69✓	.98✓	12.00	.35
150.57	151.94	1.60✓	1.94✓	20.23	.59
151.94	152.34	2.23✓	3.24✓	28.45	.83
152.34	153.89	1.38✓	.85✓	20.23	.59
153.89	155.60	1.94✓	2.00✓	22.28	.65
155.60	157.61	1.63✓	2.94✓	25.37	.74
157.61	158.92	N/A	N/A	N/A	-
158.92	161.33	2.13✓	4.38✓	35.31	1.03
161.33	163.68	.19✓	1.02✓	1.03	.03
163.68	164.56	.95✓	2.40✓	5.14	.15
164.56	166.39	.07✓	.18✓	2.06	.06
166.39	168.25	2.85✓	7.32✓	40.45	1.18
168.25	170.99	3.45✓	6.84✓	58.62	1.71
170.99	176.78	N/A	N/A	N/A	-
176.78	177.27	1.10✓	1.00✓	15.08	.44
177.27	179.53	3.53✓	6.12✓	53.48	1.56
179.53	180.96	2.48✓	6.00✓	45.25	1.32
180.96	182.70	4.05✓	6.48✓	66.50	1.94
182.70	184.95	2.50✓	4.86✓	42.51	1.24
184.95	186.63	3.08✓	2.82✓	50.39	1.47
186.63	188.34	2.85✓	2.88✓	38.39	1.12
188.34	190.80	3.45✓	4.92✓	51.42	1.50
190.80	192.79	1.43✓	3.48✓	20.23	.59
192.79	194.52	1.13✓	1.98✓	15.08	.44
194.52	195.53	3.00✓	4.26✓	51.42	1.50
195.53	197.11	2.35✓	4.74✓	37.37	1.09
197.11	197.97	3.15✓	5.04✓	49.36	1.44
197.97	200.13	2.85✓	3.48✓	38.39	1.12
200.13	201.78	1.74✓	1.39✓	30.17	.88
201.78	202.63	1.63✓	.84✓	20.23	.59
202.63	213.79	N/A	N/A	N/A	-
213.79	216.71	5.93✓	8.40✓	85.70	2.50
216.71	218.91	4.88✓	10.31✓	80.56	2.35
218.91	219.76	.23✓	1.38✓	4.11	.12
219.76	221.44	6.08✓	9.96✓	105.93	3.09
221.44	223.27	8.10✓	14.88✓	128.21	3.74
223.27	225.03	7.20✓	11.78✓	102.84	3.00
225.03	225.64	2.00✓	2.46✓	30.17	.88
225.64	227.38	.33✓	.85✓	4.11	.12
227.38	230.58	1.10✓	1.48✓	15.08	.44

SPECIAL TO MOORE BUSINESS FORMS

HOLE NO: A-30

INTERVAL		ASSAYS				
FROM	TO	PB %	ZN %	AG GM/TON	AG OZ/TON	
230.58	254.17	N/A	N/A	N/A	-	
254.17	256.06	3.75✓	7.68✓	57.59	1.68	
256.06	257.10	.28✓	.55✓	5.14	.15	
257.10	257.71	4.20✓	2.70✓	53.48	1.56	
257.71	258.59	.35✓	.66✓	7.20	.21	
258.59	260.60	1.18✓	2.52✓	20.23	.59	
260.60	263.65	.25✓	.60✓	8.23	.24	
263.65	265.33	1.55✓	3.30✓	20.23	.59	
265.33	279.44	N/A	N/A	N/A	-	
279.44	281.27	.83✓	1.90✓	7.20	.21	
281.27	282.58	.09✓	.57✓	5.14	.15	
282.58	283.01	5.10✓	12.43✓	62.39	1.82	
283.01	301.14	N/A	N/A	N/A	-	
301.14	302.67	1.88✓	1.86✓	25.37	.74	
302.67	340.22	N/A	N/A	N/A	-	
340.22	340.83	4.43✓	6.24✓	71.65	2.09	
340.83	342.29	.33✓	.37✓	6.17	.18	
342.29	342.60	4.73✓	5.76✓	65.47	1.91	
342.60	389.53	N/A	N/A	N/A	-	

K

HOLE NO: A-31
HOLE LENGTH: 217.63

LATITUDE: 10404.19
DEPARTURE: 7829.50
ELEVATION: 1278.24

AZIMUTH: 0.00
DIP: -90.00

INTERVAL		ASSAYS				
FROM	TO	PB	ZN	AG	AG	
		%	%	GM/TON	OZ/TON	
0.00	114.64	N/A	N/A	N/A	-	
114.64	115.98	4.95✓	7.05✓	68.56	2.00	
115.98	123.20	N/A	N/A	N/A	-	
123.20	124.42	1.33✓	1.18✓	25.37	.74	
124.42	133.65	N/A	N/A	N/A	-	
133.65	134.42	1.68✓	1.62✓	20.23	.59	
134.42	135.97	1.15✓	1.35✓	20.23	.59	
135.97	148.38	N/A	N/A	N/A	-	
148.38	148.80	.32✓	.94✓	6.17	.18	
148.80	168.55	N/A	N/A	N/A	-	
168.55	170.38	4.58✓	4.86✓	60.33	1.76	
170.38	171.91	3.90✓	3.60✓	44.22	1.29	
171.91	172.82	3.38✓	2.76✓	39.42	1.15	
172.82	174.04	.64✓	.34✓	15.08	.44	
174.04	217.63	N/A	N/A	N/A	-	

SPECIAL TO MOORE BUSINESS FORMS 4

HOLE NO: A-32
HOLE LENGTH: 359.21

LATITUDE: 10822.83
DEPARTURE: 7389.90
ELEVATION: 1315.03

AZIMUTH: 0.00
DIP: -90.00

DIP TESTS:	DEPTH	DIP	AZIMUTH
200	60.96 ✓	-87.00 ✓	43.20 ✓
400	121.92 ✓	-87.00 ✓	100.20 ✓
600	182.88 ✓	-87.00 ✓	42.20 ✓
800	243.84 ✓	-85.00 ✓	62.20 ✓
1160	353.57 ✓	-87.00 ✓	97.20 ✓

INTERVAL		ASSAYS				AG
FROM	TO	PB %	ZN %	AG GM/TON	02/TON	
0.00	154.99	N/A	N/A	N/A	-	-
154.99	156.36	.09 ✓	.11 ✓	2.06	.06	
156.36	158.04	1.05 ✓	2.46 ✓	14.05	.41	
158.04	158.89	3.23 ✓	3.30 ✓	42.51	1.24	
158.89	242.86	N/A	N/A	N/A	-	
242.86	243.99	1.80 ✓	3.00 ✓	25.37	.74	
243.99	244.69	5.33 ✓	8.61 ✓	115.87	3.38	
244.69	283.86	N/A	N/A	N/A	-	
283.86	285.38	1.65 ✓	2.82 ✓	26.40	.77	
285.38	286.57	4.73 ✓	5.22 ✓	70.62	2.06	
286.57	289.26	.95 ✓	.95 ✓	20.23	.59	
289.26	292.30	.80 ✓	1.11 ✓	13.03	.38	
292.30	295.35	1.14 ✓	1.08 ✓	20.23	.59	
295.35	298.40	.68 ✓	.60 ✓	14.05	.41	
298.40	301.45	.88 ✓	1.24 ✓	17.14	.50	
301.45	302.97	1.38 ✓	1.64 ✓	22.28	.65	
302.97	306.02	.10 ✓	.36 ✓	5.14	.15	
306.02	309.07	.14 ✓	.24 ✓	5.14	.15	
309.07	312.12	.10 ✓	.26 ✓	6.17	.18	
312.12	315.16	.12 ✓	.42 ✓	5.14	.15	
315.16	318.21	.14 ✓	.50 ✓	9.94	.29	
318.21	321.26	.13 ✓	.38 ✓	6.17	.18	
321.26	324.31	.13 ✓	.44 ✓	5.14	.15	
324.31	325.53	.10 ✓	.23 ✓	3.09	.09	
325.53	326.23	1.43 ✓	1.60 ✓	20.23	.59	
326.23	327.08	.94 ✓	1.48 ✓	16.11	.47	
327.08	327.66	N/A	N/A	N/A	-	
327.66	328.09	1.24 ✓	1.04 ✓	22.28	.65	
328.09	328.79	1.93 ✓	1.56 ✓	35.31	1.03	
328.79	329.18	.77 ✓	.59 ✓	15.08	.44	.52
329.18	359.21	N/A	N/A	N/A	-	

SPEER LTD MOORE BUSINESS FORMS 4

HOLE NO: A-34
 HOLE LENGTH: 273.86

LATITUDE: 11499.28
 DEPARTURE: 7034.65
 ELEVATION: 1315.30

AZIMUTH: 0.00
 DIP: -90.00

INTERVAL		ASSAYS				
FROM	TO	PB	ZN	AG	AG	
		%	%	GM/TON	0.2/TON	
0.00	232.41	N/A	N/A	N/A	-	
232.41	234.09	.75✓	1.94✓	10.97	.32	
234.09	234.70	N/A	N/A	N/A	-	
234.70	236.22	.83✓	1.02✓	9.94	.29	
236.22	237.74	.79✓	.56✓	8.23	.24	
237.74	240.79	.63✓	1.20✓	8.91	.26	
240.79	242.32	.87✓	1.44✓	13.03	.38	
242.32	243.84	.75✓	2.58✓	14.05	.41	
243.84	245.36	N/A	N/A	N/A	-	
245.36	247.19	.69✓	1.60✓	9.94	.29	
247.19	248.72	3.68✓	9.30✓	60.33	1.76	
248.72	251.76	1.30✓	1.98✓	20.23	.59	
251.76	254.81	1.38✓	1.86✓	20.23	.59	
254.81	257.86	N/A	N/A	N/A	-	
257.86	259.38	1.03✓	1.32✓	15.08	.44	
259.38	273.86	N/A	N/A	N/A	-	

HOLE NO: A-35
 HOLE LENGTH: 389.84

LATITUDE: 10777.92
 DEPARTURE: 7348.92
 ELEVATION: 1313.70

AZIMUTH: 0.00
 DIP: -90.00

INTERVAL		ASSAYS				
FROM	TO	PB	ZN	AG		
		%	%	GM/TON		AG O ₂ /TON
0.00	158.50	N/A	N/A	N/A		
158.50	158.80	.09	.07	5.14		.15
158.80	159.72	6.00	3.72	82.61		2.41
159.72	161.73	1.60	.37	43.54		1.27
161.73	163.53	4.28	3.72	65.47		1.91
163.53	164.20	N/A	N/A	N/A		-
164.20	164.56	.39	.04	15.08		.44
164.56	165.78	7.35	7.75	95.64		2.79
165.78	166.39	1.60	1.64	37.37		1.09
166.39	167.03	N/A	N/A	N/A		-
167.03	168.86	3.53	3.66	50.39		1.47
168.86	169.56	1.60	1.64	22.28		.65
169.56	171.48	5.33	4.68	75.76		2.21
171.48	172.52	.45	.62	9.94		.29
172.52	285.60	N/A	N/A	N/A		-
285.60	288.65	.83	.72	15.08		.44
288.65	290.17	1.25	.86	18.17		.53
290.17	325.56	N/A	N/A	N/A		-
325.56	327.17	.13	.06	5.14		.75
327.17	327.96	N/A	N/A	N/A		-
327.96	328.57	1.10	1.18	23.31		.68
328.57	329.64	N/A	N/A	N/A		-
329.64	330.34	.20	.14	1.03		.03
330.34	331.68	1.23	1.02	19.20		.56
331.68	334.67	.53	.56	9.94		.29
334.67	337.57	.75	.63	8.91		.26
337.57	339.39	2.10	2.58	26.40		.77
339.39	341.28	1.35	2.00	20.23		.59
341.28	343.39	N/A	N/A	N/A		-
343.39	343.88	.48	.59	10.97		.32
343.88	346.86	3.83	4.44	45.25		1.32
346.86	347.78	.50	.42	9.94		.29
347.78	349.00	1.25	1.74	15.08		.44
349.00	352.04	.27	.52	6.17		.18
352.04	355.09	.15	.58	5.14		.15
355.09	356.25	N/A	N/A	N/A		-
356.25	357.07	3.75	3.90	46.28		1.35
357.07	358.14	.20	.37	4.11		.12
358.14	361.19	.17	.44	4.11		.12
361.19	364.78	N/A	N/A	N/A		-
364.78	366.37	1.80	1.60	22.28		.65
366.37	367.89	1.75	1.42	20.23		.59
367.89	389.84	N/A	N/A	N/A		-

SPECIFIC MODEL BUSINESS FORM 4

HOLE NO: A-37
 HOLE LENGTH: 158.50

LATITUDE: 10232.49
 DEPARTURE: 7833.75
 ELEVATION: 1266.44

AZIMUTH: 0.00
 DIP: -90.00

INTERVAL		ASSAYS				
FROM	TO	PB	ZN	AG	AG	
		%	%	GM/TON	GM/TON	
0.00	65.23	N/A	N/A	N/A	-	
65.23	68.28	.97✓	1.12✓	16.11	.47	
68.28	70.41	.77✓	.74✓	15.08	.44	
70.41	71.63	.35✓	.72✓	9.94	.29	
71.63	72.39	4.58✓	5.40✓	60.33	1.76	
72.39	74.07	.68✓	.70✓	18.17	.53	
74.07	75.59	7.35✓	6.12✓	73.70	2.15	
75.59	76.35	2.23✓	3.60✓	30.17	.88	
76.35	77.27	2.63✓	1.96✓	30.17	1.88	
77.27	79.25	7.20✓	9.44✓	63.42	1.85	
79.25	80.16	2.03✓	2.82✓	22.28	.63	
80.16	82.60	8.41✓	12.75✓	95.64	2.79	
82.60	84.12	5.55✓	7.32✓	57.59	1.68	
84.12	85.56	1.04✓	1.16✓	17.14	.50	
85.56	86.35	9.39✓	14.20✓	101.81	2.97	
86.35	89.31	2.78✓	5.46✓	35.31	1.03	
89.31	92.35	2.50✓	5.16✓	35.31	1.03	
92.35	95.40	4.05✓	5.88✓	48.33	1.41	
95.40	98.45	2.50✓	4.14✓	37.37	1.09	
98.45	101.50	1.12✓	2.28✓	16.11	.47	
101.50	103.08	2.15✓	3.12✓	25.37	.74	
103.08	104.85	4.13✓	6.00✓	50.39	1.47	
104.85	106.68	.50✓	.96✓	6.17	.18	
106.68	108.69	1.23✓	1.34✓	15.08	.44	
108.69	112.90	.39✓	.58✓	6.17	.18	
112.90	114.48	3.83✓	4.68✓	53.48	1.56	
114.48	117.65	.29✓	.36✓	8.23	.24	
117.65	120.70	.07✓	.20✓	5.14	.15	
120.70	122.59	.40✓	.60✓	9.94	.29	
122.59	123.78	2.08✓	2.88✓	27.42	.80	
123.78	124.91	1.60✓	1.72✓	20.23	.59	
124.91	126.19	3.23✓	6.60✓	38.39	1.12	
126.19	158.50	N/A	N/A	N/A	-	
108.69	112.35	N/A	N/A	N/A	-	

IC

SPECIAL ORDER BUSINESS FORM 4

HOLE NO: A-38
 HOLE LENGTH: 363.32

LATITUDE: 10734.00
 DEPARTURE: 7307.52
 ELEVATION: 1312.47

AZIMUTH: 0.00
 DIP: -90.00

INTERVAL		ASSAYS				
FROM	TO	PB	ZN	AG	AG	
		%	%	GM/TON	02/TON	
0.00	184.59	N/A	N/A	N/A	-	
184.59	185.32	1.80✓	1.40✓	29.14	.85	
185.32	187.91	2.50✓	3.00✓	42.51	1.24	
187.91	189.28	1.03✓	.98✓	15.08	.44	
189.28	192.12	3.23✓	2.40✓	40.45	1.18	
192.12	192.54	N/A	N/A	N/A	-	
192.54	195.22	.90✓	1.00✓	9.94	.29	
195.22	215.04	N/A	N/A	N/A	-	
215.04	216.41	6.08✓	4.86✓	77.82	2.27	
216.41	225.55	N/A	N/A	N/A	-	
225.55	227.99	8.25✓	8.55✓	86.73	2.53	
227.99	230.58	5.63✓	7.61✓	70.62	2.06	
230.58	271.27 ^{293.71}	N/A	N/A	N/A	-	
271.27	274.44	1.18✓	1.56✓	13.03	.38	
274.44	275.42	8.55✓	5.16✓	95.64	2.79	
275.42	276.18	4.95✓	.59✓	55.53	1.62	
276.18	278.22	1.58✓	.60✓	17.14	.50	
278.22	279.26	4.50✓	7.40✓	62.39	1.82	
279.26	280.72	.14✓	.18✓	7.20	.21	
280.72	282.55	.14✓	.16✓	6.17	.18	
282.55	284.20	7.65✓	9.75✓	105.93	3.09	
284.20	287.24	.43✓	.42✓	9.94	.29	
287.24	290.02	1.20✓	.78✓	19.20	.56	
290.02	291.85	.80✓	1.20✓	15.08	.44	
291.85	292.91	.63✓	.58✓	10.97	.32	
292.91	293.52	5.40✓	4.86✓	60.33	1.76	
293.52	295.14	.52✓	.85✓	9.26	.27	
295.14	296.27	4.35✓	4.50✓	58.62	1.71	
296.27	298.22	2.20✓	1.56✓	36.34	1.06	
298.22	341.07	N/A	N/A	N/A	-	
341.07	342.38	2.10✓	1.94✓	25.37	.74	
342.38	343.30	.34✓	.18✓	7.20	.21	
343.30	343.84	1.98✓	1.76✓	30.17	.88	
343.84	346.65	.58✓	.45✓	10.97	.32	
346.65	348.69	2.10✓	1.98✓	27.42	.80	
348.69	351.50	3.60✓	3.00✓	47.31	1.38	
351.50	352.35	.60✓	.58✓	5.14	.15	
352.35	353.54	2.00✓	2.00✓	30.17	.88	
353.54	363.32	N/A	N/A	N/A	-	

SHEET 10 MORE BUSINESS FORMS 4

HOLE NO: A-39
 HOLE LENGTH: 234.10

LATITUDE: 10188.24
 DEPARTURE: 7790.73
 ELEVATION: 1262.24

AZIMUTH: 0.00
 DIP: -90.00

INTERVAL		ASSAYS				
FROM	TO	PB	ZN	AG		AG
		%	%	GM/TON		OZ/TON
0.00	88.30	N/A	N/A	N/A		-
88.30	89.92	1.00 ✓	.69 ✓	17.14		.50
89.92	98.60	N/A	N/A	N/A		-
98.60	99.36	1.40 ✓	1.10 ✓	20.23		.59
99.36	100.22	.23 ✓	.23 ✓	5.14		.15
100.22	102.44	1.15 ✓	.88 ✓	17.14		.50
102.44	105.00	N/A	N/A	N/A		-
105.00	107.23	.93 ✓	1.44 ✓	15.08		.44
107.23	108.57	2.35 ✓	2.40 ✓	20.23		.59
108.57	110.12	.14 ✓	.23 ✓	12.00		.35
110.12	113.08	2.93 ✓	2.22 ✓	35.31		1.03
113.08	114.82	1.65 ✓	1.16 ✓	25.37		.74
114.82	116.65	2.38 ✓	2.76 ✓	32.22		.94
116.65	117.96	.33 ✓	.29 ✓	6.17		.18
117.96	118.66	.84 ✓	1.04 ✓	9.94		.29
118.66	234.09	N/A	N/A	N/A		-

HOLE NO: A-41
 HOLE LENGTH: 384.10

LATITUDE: 10689.07
 DEPARTURE: 7267.54
 ELEVATION: 1318.63

AZIMUTH: 0.00
 DIP: -90.00

INTERVAL		ASSAYS			
FROM	TO	PB	ZN	AG	
		%	%	GM/TON	AG OZ/TON
0.00	217.93	N/A	N/A	N/A	
217.93	219.36	1.60✓	2.28✓	27.42	.80
219.36	221.59	.13✓	.11✓	8.23	.24
221.59	222.66	2.45✓	1.50✓	51.42	1.50
222.66	223.72	6.45✓	7.07✓	115.87	3.38
223.72	225.86	9.00✓	8.53✓	121.01	3.53
225.86	228.30	.38✓	.27✓	12.00	.35
228.30	229.82	1.50✓	.49✓	26.40	.77
229.82	231.34	.15✓	.17✓	2.06	.06
231.34	232.14	6.15✓	7.20✓	90.84	2.65
232.14	233.66	.63✓	.28✓	9.94	.29
233.66	235.61	.50✓	.34✓	9.94	.29
235.61	236.04	N/A	N/A	N/A	-
236.04	238.81	1.15✓	.80✓	15.08	.44
238.81	239.88	.33✓	.24✓	7.20	.21
239.88	241.10	N/A	N/A	N/A	-
241.10	243.23	.58✓	.36✓	8.23	.24
243.23	256.25	N/A	N/A	N/A	-
256.25	257.37	.35✓	.20✓	10.97	.32
257.37	258.10	.01✓	.01✓	1.03	.03
258.10	259.26	.35✓	.26✓	9.94	.29
259.26	260.79	5.48✓	6.48✓	72.67	2.12
260.79	262.31	.18✓	.23✓	6.17	.18
262.31	263.80	.35✓	.44✓	9.94	.29
263.80	266.15	2.20✓	1.80✓	35.31	1.03
266.15	266.70	.28✓	.31✓	7.20	.21
266.70	279.04	N/A	N/A	N/A	-
279.04	281.18	1.18✓	1.24✓	20.23	.59
281.18	282.40	4.13✓	4.38✓	58.62	1.71
282.40	283.92	1.50✓	1.64✓	26.40	.77
283.92	285.45	.55✓	.23✓	12.00	.35
285.45	286.30	.09✓	.08✓	1.03	.63
286.30	287.88	.45✓	.30✓	9.94	.29
287.88	288.77	.04✓	.07✓	1.03	.03
288.77	289.50	1.23✓	1.20✓	16.11	.47
289.50	384.05	N/A	N/A	N/A	-

SPEEDY LO MOORE BUSINESS FORMS 4

143

HOLE NO: A-42
 HOLE LENGTH: 136.70

LATITUDE: 10143.65
 DEPARTURE: 7748.71
 ELEVATION: 1264.70

AZIMUTH: 0.00
 DIP: -90.00

INTERVAL		ASSAYS				
FROM	TO	PB	ZN	AG	AG	
		%	%	GM/TON	OZ/TON	
0.00	112.07	N/A	N/A	N/A	-	
112.07	115.21	1.25✓	.99✓	18.17	.53	
115.21	117.35	3.00✓	3.60✓	40.45	1.18	
117.35	117.96	7.20✓	10.00✓	88.79	2.59	
117.96	118.32	3.45✓	4.32✓	40.45	1.18	
118.32	120.40	1.98✓	1.71✓	25.37	.74	
120.40	121.92	1.58✓	1.47✓	20.23	.59	
121.92	123.44	1.80✓	1.34✓	25.37	.74	
123.44	124.75	1.40✓	1.44✓	20.23	.59	
124.75	125.94	N/A	N/A	N/A	-	
125.94	126.64	3.15✓	3.66✓	35.31	1.03	
126.64	136.70	N/A	N/A	N/A	-	

SPED UP MOORE BUSINESS FORMS 4

10/AV

HOLE NO: A-45
HOLE LENGTH: 235.31

LATITUDE: 10658.86
DEPARTURE: 7738.69
ELEVATION: 1292.05

AZIMUTH: 0.00
DIP: -90.00

DIP TESTS:	DEPTH	DIP	AZIMUTH
✓60.96	-89.00 ✓	62.20	33.0
✓121.92	-86.00 ✓	57.20	
✓195.07	-86.00	91.20	
	-76.8		

INTERVAL		ASSAYS				
FROM	TO	PB %	ZN %	AG GM/TON	AG OZ/TON	
0.00	44.50	N/A	N/A	N/A	-	
44.50	50.90	5.93 ✓	7.44 ✓	80.56	2.35	
50.90	51.82	.73 ✓	3.18 ✓	9.94	.29	
51.82	53.04	1.22	2.33 ✓	5.28 ✓	28.45	.83
53.04	55.93	2.89	2.33 ✓	7.20	31.19	.91
55.93	57.91	1.98	3.90 ✓	5.22 ✓	49.36	1.44
57.91	60.96	3.05	4.43 ✓	12.10 ✓	60.33	1.76
60.96	62.79		4.50 ✓	5.40	54.51	1.59
62.79	64.16		N/A	N/A	N/A	-
64.16	66.45		6.00 ✓	9.60 ✓	80.56	2.35
66.45	67.21		2.30 ✓	4.42 ✓	19.20	.56
67.21	73.15		N/A	N/A	N/A	-
73.15	76.20		.42 ✓	.98 ✓	9.94	.29
76.20	77.72	1.52	6.90 ✓	14.20 ✓	103.87	3.03
77.72	79.25	1.53	8.25 ✓	16.20 ✓	100.78	2.94
79.25	81.08	1.83	8.63 ✓	16.80 ✓	121.01	3.53
81.08	83.82	2.74	8.74 ✓	17.00 ✓	130.95	3.82
83.82	84.43	.61	7.50 ✓	15.60 ✓	100.78	2.94
84.43	86.56	2.13	1.25	2.00 ✓	9.94	.29
86.56	87.93	1.37	3.60 ✓	6.60 ✓	56.56	1.65
87.93	166.12		N/A	N/A	N/A	-
166.12	167.79	1.67	.08 ✓	.12	5.14	.15
167.79	169.47	1.68	.19 ✓	.59 ✓	5.14	.15
169.47	171.30	1.83	3.23 ✓	5.28 ✓	37.37	1.09
171.30	172.52	1.22	.70 ✓	2.28 ✓	8.23	.24
172.52	177.70		N/A	N/A	N/A	-
177.70	178.77		1.48 ✓	.86 ✓	19.20	.56
178.77	190.20		N/A	N/A	N/A	-
190.20	193.85	3.65	1.88 ✓	3.84 ✓	34.28	1.00
193.85	195.07	1.22	6.23 ✓	8.82 ✓	95.64	2.79
195.07	196.60	1.53	1.80 ✓	4.80 ✓	38.39	1.12
196.60	197.21	.61	4.95 ✓	8.28 ✓	97.70	2.85
197.21	198.91		N/A	N/A	N/A	-
198.91	201.17	2.26	1.98 ✓	1.98 ✓	30.17	.88
201.17	202.69	1.52	1.04 ✓	.63 ✓	15.08	.44
202.69	204.22	1.53	6.53 ✓	3.66 ✓	60.33	1.76
204.22	207.26	3.04	.97 ✓	.46 ✓	15.08	.44
207.26	208.79	1.53	.27 ✓	.37	8.91	.26
208.79	210.31	1.52	.94 ✓	1.30	15.08	.44
210.31	210.92	.61	2.20 ✓	1.50	30.17	.88
210.92	212.45	1.53	2.20 ✓	3.24 ✓	32.22	.94
212.45	213.21	.76	1.63 ✓	3.12 ✓	30.17	.88
213.21	235.31		N/A	N/A	N/A	-

SPEURLO MOORE BUSINESS FORMS

HOLE NO: A-50
HOLE LENGTH: 203.30

LATITUDE: 10104.55
DEPARTURE: 7877.98
ELEVATION: 1252.61

AZIMUTH: 0.00
DIP: -90.00

INTERVAL		ASSAYS				
FROM	TO	PB	ZN	AG		AG
		%	%	GM/TON		OZ/TON
0.00	21.34	N/A	N/A	N/A		-
21.34	23.77	2.45✓	1.88✓	27.42		.80
23.77	26.37	2.48✓	1.92✓	34.28		1.00
26.37	28.50	N/A	N/A	N/A		-
28.50	29.57	2.35✓	2.46✓	30.17		.88
29.57	48.31	N/A	N/A	N/A		-
48.31	49.19	3.15✓	3.00✓	35.31		1.03
49.19	49.41	N/A	N/A	N/A		-
49.41	50.90	2.30✓	1.96✓	30.17		.88
50.90	53.34	.85✓	.72✓	19.20		.56
53.34	203.30	N/A	N/A	N/A		-

SPEER O MOORE BUSINESS FORMS 4

HOLE NO: A-51
 HOLE LENGTH: 366.98

LATITUDE: 10906.31
 DEPARTURE: 7303.36
 ELEVATION: 1323.02

AZIMUTH: 0.00
 DIP: -90.00

DIP TESTS:	DEPTH	DIP	AZIMUTH
	60.96	-84.30	84.50
	182.88	-82.30	95.20
	243.84	-79.15	102.50
	366.98	-79.30	127.00

INTERVAL		ASSAYS			AG 02/TON
FROM	TO	PB %	ZN %	AG GM/TON	
0.00	169.77	N/A	N/A	N/A	
169.77	171.30	1.00✓	1.12✓	10.97	.32
171.30	172.82	1.08✓	1.08✓	15.08	.44
172.82	173.74	.70✓	.54✓	9.94	.29
173.74	174.65	.29✓	.32✓	6.17	.18
174.65	174.96	1.02✓	.86✓	32.22	.94
174.96	204.67	N/A	N/A	N/A	-
204.67	205.59	1.03✓	.90✓	10.97	.32
205.59	206.47	N/A	N/A	N/A	-
206.47	207.08	1.88✓	1.34✓	21.25	.62
207.08	207.57	N/A	N/A	N/A	-
207.57	209.40	2.85✓	1.72✓	55.53	1.62
209.40	210.37	8.05✓	6.60✓	113.12	3.30
210.37	213.36	.75✓	1.70✓	15.08	.44
213.36	213.97	4.28✓	4.26✓	54.51	1.59
213.97	297.48	N/A	N/A	N/A	-
297.48	299.62	.90✓	1.34✓	13.03	.38
299.62	301.11	2.38✓	2.88✓	38.39	1.12
301.11	301.29	N/A	N/A	N/A	-
301.29	304.10	.80✓	.62✓	12.00	.35
304.10	307.85	.18✓	.18✓	4.11	.12
307.85	308.31	1.23✓	.90✓	15.08	.44
308.31	311.35	.18✓	.27✓	5.14	.15
311.35	313.85	.83✓	.70✓	12.00	.35
313.85	324.79	N/A	N/A	N/A	-
324.79	325.68	2.05✓	1.76✓	21.25	.62
325.68	335.34	N/A	N/A	N/A	-
335.34	336.26	2.35✓	2.28✓	35.31	1.03
336.26	337.60	N/A	N/A	N/A	-
337.60	338.66	1.95✓	1.62✓	30.17	.88
338.66	340.16	.03✓	.16✓	2.06	.06
340.16	341.38	1.90✓	1.84✓	27.42	.80
341.38	343.20	.20✓	.27✓	5.14	.15
343.20	344.18	.83✓	.82✓	10.97	.32
344.18	345.34	.69✓	.86✓	12.00	.35
345.34	346.04	4.28✓	6.12✓	48.33	1.41
346.04	347.32	1.33✓	1.60✓	20.23	.59
347.32	366.98	N/A	N/A	N/A	-

HOLE NO: A-52
HOLE LENGTH: 261.82

LATITUDE: 10702.92
DEPARTURE: 7782.06
ELEVATION: 1299.89

AZIMUTH: 0.00
DIP: -90.00

DIP TESTS:	DEPTH	DIP	AZIMUTH
	✓60.96	-90.00✓	0.00 33.0
	✓121.92	-85.30✓	67.00✓
	✓182.88	-79.00✓	84.00✓
	✓237.74	-74.00✓	82.00✓

INTERVAL		ASSAYS				AG
FROM	TO	PB	ZN	AG	AG	
		%	%	GM/TON	02/TON	
0.00	78.03	N/A	N/A	N/A	-	
78.03	78.33	11.00✓	20.45✓	171.40	5.00	
78.33	85.04	N/A	N/A	N/A	-	
85.04	85.89	1.75✓	2.22✓	27.42	.80	
85.89	86.11	N/A	N/A	N/A	-	
86.11	87.78	8.18✓	10.72✓	110.04	3.21	
87.78	143.87	N/A	N/A	N/A	-	
143.87	146.91	.25✓	.55✓	7.20	.21	
146.91	149.11	.18✓	.44✓	7.20	.21	
149.11	157.58	N/A	N/A	N/A	-	
157.58	158.65	1.07 3.90✓	5.46✓	50.39	1.47	
158.65	160.78	2.13 3.23✓	5.52✓	45.25	1.32	
160.78	175.41	N/A	N/A	N/A	-	
175.41	176.48	1.07 4.65✓	4.20✓	50.39	1.47	
176.48	179.53	3.05 2.50✓	3.84✓	41.48	1.21	
179.53	181.66	2.13 3.83✓	4.98✓	53.48	1.56	
181.66	183.03	1.37 2.45✓	3.36✓	41.48	1.21	
183.03	184.10	1.07 6.75✓	8.16✓	77.82	2.27	
184.10	186.08	1.98 1.23✓	1.94✓	20.23	.59	
186.08	187.91	1.83 .60✓	.99✓	9.94	.29	
187.91	189.22	1.31 1.28	1.10✓	13.03	.38	
189.22	192.91	3.69 .27✓	.40✓	7.20	.21	
192.91	194.86	1.95 .45✓	.56✓	8.23	.24	
194.86	196.75	1.89 .32✓	.40✓	4.11	.12	
196.75	199.80	3.05 .48✓	.16✓	5.14	.15	
199.80	201.50	1.70 .27✓	.37✓	7.20	.21	
201.50	209.09	N/A	N/A	N/A	-	
209.09	210.77	.05✓	.15✓	2.06	.06	
210.77	261.82	N/A	N/A	N/A	-	

SPEER LO MOORE BUSINESS FORMS

HOLE NO: A-53
 HOLE LENGTH: 357.23

LATITUDE: 10814.20
 DEPARTURE: 7550.77
 ELEVATION: 1308.52

AZIMUTH: 0.00 ✓
 DIP: -90.00 ✓

DIP TESTS:	DEPTH	DIP	AZIMUTH
	32.92 ✓	-88.00 ✓	84.20 ✓
	75.60 ✓	-89.00 ✓	91.20 ✓
	124.36 ✓	-87.00 ✓	54.50 ✓

INTERVAL		PB %	ASSAYS			AG OZ/TON
FROM	TO		ZN %	AG GM/TON		
0.00	140.67	N/A	N/A	N/A		
140.67	141.73	1.06	7.05 ✓	13.81 ✓	113.12	3.30
141.73	145.08	3.35	6.23 ✓	13.55 ✓	100.78	2.94
145.08	145.69	.61	3.90 ✓	8.53 ✓	55.53	1.62
145.69	147.22	1.53	3.08 ✓	7.42 ✓	49.36	1.44
147.22	148.74	1.52	6.90 ✓	17.20 ✓	100.78	2.94
148.74	149.96	1.22	10.57 ✓	18.79 ✓	194.71	5.68
149.96	151.79	1.83	1.13 ✓	2.88 ✓	15.08	.44
151.79	153.01	1.22	2.25 ✓	4.20 ✓	30.17	.88
153.01	154.84	1.83	2.00 ✓	4.02 ✓	27.42	.80
154.84	155.91	1.07	1.50 ✓	2.70 ✓	18.17	.53
155.91	157.89	1.98	3.90 ✓	3.78 ✓	41.48	1.21
157.89	159.93	2.04	.70 ✓	1.04 ✓	13.03	.38
159.93	161.42	1.49	1.68 ✓	4.02 ✓	22.28	.65
161.42	166.82	5.10	N/A	N/A	N/A	
166.82	169.01	2.19	.52 ✓	1.20 ✓	7.20	.21
169.01	171.36	2.35	N/A	N/A	N/A	
171.36	172.97	1.61	.57 ✓	1.56 ✓	9.94	.29
172.97	234.39		N/A	N/A	N/A	
234.39	237.04	2.65	.38 ✓	.78 ✓	8.91	.26
237.04	238.29	1.25	3.68 ✓	6.96 ✓	52.45	1.53
238.29	240.15	1.86	.74 ✓	.68 ✓	19.20	.56
240.15	243.23	3.08	4.43 ✓	6.00 ✓	62.39	1.82
243.23	244.45	1.22	5.40 ✓	11.10 ✓	94.61	2.76
244.45	245.67	1.22	2.00 ✓	3.96 ✓	35.31	1.03
245.67	248.29	2.62	2.28 ✓	1.80 ✓	35.31	1.03
248.29	251.34	3.05	1.55 ✓	1.34 ✓	27.42	.80
251.34	252.37	1.03	4.73 ✓	7.20 ✓	67.53	1.97
252.37	254.87	2.50	5.03 ✓	9.59 ✓	82.61	2.41
254.87	257.25	2.42	4.95 ✓	8.09 ✓	65.47	1.91
257.25	258.53	1.28	4.58 ✓	7.20 ✓	64.45	1.88
258.53	259.99	1.46	5.33 ✓	9.88 ✓	79.53	2.32
259.99	262.13	2.14	.27 ✓	.33 ✓	9.94	.29
262.13	263.62	1.49	.75 ✓	2.34 ✓	15.08	.44
263.62	264.66	1.09	5.10 ✓	9.83 ✓	65.47	1.91
264.66	267.52	2.86	.53 ✓	1.38 ✓	21.25	.62
267.52	268.96	1.44	5.55 ✓	11.50 ✓	75.76	2.21
268.96	270.36	1.40	.60 ✓	.69 ✓	18.17	.53
270.36	272.40	2.04	5.70 ✓	8.71 ✓	65.47	1.91
272.40	273.71	1.31	.27 ✓	.28 ✓	9.94	.29
273.71	277.09	3.38	.19 ✓	.80 ✓	9.94	.29
277.09	278.31	1.22	.27 ✓	1.38 ✓	9.94	.29
278.31	280.23	1.92	.07 ✓	.98 ✓	5.14	1.15
280.23	281.97	1.74	.08 ✓	1.06 ✓	5.14	.15
281.97	283.80	1.83	.89 ✓	1.98 ✓	21.25	.62

SPRINTED MOORE BUSINESS FORMS 4

HOLE NO: A-55 LATITUDE: 10575.80 AZIMUTH: 0.00
 HOLE LENGTH: 217.93 DEPARTURE: 7827.11 DIP: -90.00
 ELEVATION: 1288.66

DIP TESTS: DEPTH DIP AZIMUTH
 60.96 ✓ -84.00 ✓ 67.20 ✓
 121.92 ✓ -78.00 ✓ 60.20 ✓
 195.07 ✓ -75.30 ✓ 56.20 ✓

INTERVAL		ASSAYS			AG OZ/TON
FROM	TO	PB %	ZN %	AG GM/TON	
0.00	149.05	N/A	N/A	N/A	-
149.05	150.24	1.64 ✓	2.64 ✓	35.31	1.03
150.24	151.33	.85 ✓	1.66 ✓	14.05	.41
151.33	152.86	3.00 ✓	7.44 ✓	45.25	1.32
152.86	166.88	N/A	N/A	N/A	-
166.88	167.30	.90 ✓	.94 ✓	8.91	.26
167.30	169.01	6.00 ✓	7.82 ✓	73.70	2.15
169.01	169.38	.30 ✓	.62 ✓	5.14	.15
169.38	174.74	N/A	N/A	N/A	-
174.74	175.20	1.08 ✓	2.76 ✓	17.14	.50
175.20	180.53	N/A	N/A	N/A	-
180.53	181.90	1.23 ✓	2.88 ✓	20.23	.59
181.90	182.88	5.33 ✓	5.16 ✓	51.42	1.50
182.88	184.40	1.23 ✓	1.38 ✓	25.37	.74
184.40	187.33	1.15 ✓	1.18 ✓	16.11	.47
187.33	189.89	1.35 ✓	1.72 ✓	17.14	.50
189.89	192.94	.83 ✓	.74 ✓	7.20	.21
192.94	194.95	1.45 ✓	1.72 ✓	22.28	.65
194.95	196.29	.37 ✓	.26 ✓	9.94	.29
196.29	217.93	N/A	N/A	N/A	-

HOLE NO: A-56 LATITUDE: 10786.97 AZIMUTH: 0.00
 HOLE LENGTH: 343.20 DEPARTURE: 7691.92 DIP: -90.00
 ELEVATION: 1310.39

DIP TESTS:	DEPTH	DIP	AZIMUTH
	60.96✓	-90.00✓	0.00✓
	121.92✓	-81.00✓	126.20✓
	182.88✓	-81.00✓	116.20✓
	243.84✓	-83.00✓	161.20✓

INTERVAL		ASSAYS				AG
FROM	TO	PB	ZN	AG		02/TON
		%	%	GM/TON		
0.00	96.47	N/A	N/A	N/A		-
96.47	98.15	8.40✓	12.14✓	97.70		2.85
98.15	100.28	4.05✓	7.44✓	45.25		1.32
100.28	102.17	2.28✓	4.98✓	34.28		1.00
102.17	103.02	1.10✓	4.02✓	8.23		.24
103.02	103.94	1.93✓	4.92✓	30.17		.88
103.94	106.07	1.98✓	3.54✓	30.17		.88
106.07	107.29	5.25✓	1.26✓	44.22		1.29
107.29	109.42	1.85✓	1.52✓	22.28		.65
109.42	110.34	.05✓	4.02✓	1.03		.03
110.34	112.17	2.25✓	6.72✓	35.31		1.03
112.17	114.00	.13✓	.39✓	3.09		.09
114.00	115.21	.07✓	.44✓	2.06		.06
115.21	118.26	1.98✓	3.78✓	30.17		.88
118.26	119.42	1.98✓	3.72✓	29.14		.85
119.42	121.31	1.78✓	4.08✓	26.40		.77
121.31	122.53	2.30✓	7.08✓	37.37		1.09
122.53	124.36	1.73✓	4.20✓	28.45		.83
124.36	126.19	2.85✓	5.28	45.25		1.32
126.19	129.24	2.93✓	5.58✓	45.25		1.32
129.24	132.28	1.65✓	3.84✓	27.42		.80
132.28	134.42	2.50✓	5.46✓	33.25		.97
134.42	135.64	1.98✓	5.28	29.14		.85
135.64	137.16	1.00✓	3.72✓	15.08		.44
137.16	139.29	3.23✓	7.08✓	54.51		1.59
139.29	141.12	3.30✓	6.00✓	44.22		1.29
141.12	143.16	3.98✓	3.30	54.51		1.59
143.16	145.05	N/A	N/A	N/A		-
145.05	146.91	2.40✓	4.44✓	40.45		1.18
146.91	148.74	1.00✓	3.18✓	25.37		.74
148.74	150.39	.89✓	1.02✓	21.25		.62
150.39	151.24	4.28✓	2.00✓	52.45		1.53
151.24	153.31	5.25✓	7.93✓	64.45		1.88
153.31	154.84	.90✓	4.56✓	14.05		.41
154.84	156.36	3.74✓	7.92✓	51.42		1.50
156.36	157.58	3.68✓	9.05✓	60.33		1.76
157.58	158.59	3.08✓	7.44✓	40.45		1.18
158.59	161.39	N/A	N/A	N/A		-
161.39	163.04	5.33✓	7.56✓	74.73		2.18
163.04	166.12	N/A	N/A	N/A		-
166.12	166.97	6.83✓	15.65✓	121.01		3.53
166.97	167.94	N/A	N/A	N/A		-
167.94	169.62	6.75✓	11.64✓	100.78		2.94
169.62	170.38	1.13✓	4.56✓	17.14		.50

375

SPECIFIC TO MOORE BUSINESS FORMS 4

HOLE NO: A-56

INTERVAL		ASSAYS			
FROM	TO	PB %	ZN %	AG GM/TON	AG OZ/TON
170.38	172.33	7.13 ✓	12.50 ✓	111.07	3.24
172.33	173.74	2.35 ✓	4.44 ✓	31.19	0.91
173.74	177.30	6.30 ✓	13.51 ✓	95.64	2.79
177.30	179.83	N/A	N/A	N/A	-
179.83	181.36	3.68 ✓	13.15 ✓	80.56	2.35
181.36	184.53	N/A	N/A	N/A	-
184.53	185.32	2.93 ✓	8.04 ✓	70.62	2.06
185.32	185.93	1.08 ✓	1.80 ✓	15.08	.44
185.93	188.67	6.00 ✓	9.37 ✓	95.64	2.79
188.67	191.41	4.50 ✓	8.16 ✓	77.82	2.27
191.41	193.85	6.75 ✓	9.42 ✓	93.93	2.74
193.85	195.07	6.45 ✓	10.65 ✓	104.90	3.06
195.07	196.23	.93 ✓	1.56 ✓	14.05	.41
196.23	202.30	N/A	N/A	N/A	-
202.30	203.61	1.33 ✓	2.00 ✓	18.17	.53
203.61	205.13	2.70 ✓	5.40 ✓	34.28	1.00
205.13	265.05	N/A	N/A	N/A	-
265.05	265.82	.05 ✓	3.90 ✓	5.14	.75
265.82	266.67	3.98 ✓	6.48 ✓	48.33	1.41
266.67	268.01	.50 ✓	1.32 ✓	8.23	.24
268.01	297.42	N/A	N/A	N/A	-
297.42	298.49	1.95 ✓	2.46 ✓	30.17	.88
298.49	300.14	4.35 ✓	5.28 ✓	63.42	1.85
300.14	300.72	N/A	N/A	N/A	-
300.72	302.06	4.50 ✓	5.40 ✓	75.76	2.21
302.06	343.20	N/A	N/A	N/A	-

12.30

+

DIAMOND DRILL LOG MASTER FILE

HOLE NO: A-57

LATITUDE: 11372.97

AZIMUTH: 0.00

DEPARTURE: 7080.84

DIP: -90.00

ELEVATION: 1325.54

INTERVAL		ASSAYS				AG
FROM	TO	PB %	ZN %	AG GM/TON	AG OZ/Ton	
0.00	208.61	N/A	N/A	N/A	-	
208.61	209.18	.12✓	.21✓	4.11	.12	
209.18	211.56	1.45✓	2.70✓	21.25	.62	
211.56	218.33	N/A	N/A	N/A	-	
218.33	218.63	2.30✓	4.40	35.31	1.03	4.44
218.63	219.55	N/A	N/A	N/A	-	
219.55	220.55	1.05✓	2.46✓	15.08	.44	
220.55	221.41	.09✓	.13✓	2.06	.06	
221.41	222.69	1.43✓	2.70✓	16.11	.47	
222.69	223.21	N/A	N/A	N/A	-	
223.21	224.97	1.50✓	3.00✓	28.45	.83	
224.97	226.44	.93✓	1.76✓	12.00	.35	
226.44	228.26	N/A	N/A	N/A	-	
228.26	228.54	.84✓	.99✓	13.03	.38	
228.54	229.42	1.33✓	2.52✓	17.14	.50	
229.42	231.04	1.28✓	2.94✓	18.17	.53	
231.04	233.17	1.35✓	3.06✓	20.23	.59	
233.17	235.73	1.40✓	2.88✓	21.25	.62	
235.73	237.59	.48✓	.42✓	8.23	.24	
237.59	240.79	1.50✓	1.28✓	19.20	.56	
240.79	241.92	N/A	N/A	N/A	-	
241.92	244.14	.83✓	1.30✓	15.08	.44	
244.14	246.67	1.13✓	1.50✓	20.23	.59	
246.67	248.93	2.33✓	3.18✓	34.28	1.00	
248.93	251.28	1.08✓	1.60✓	18.17	.53	
251.28	254.45	1.35✓	2.40✓	20.23	.59	
254.45	255.85	.90✓	1.24✓	12.00	.35	
255.85	257.25	1.73✓	3.06✓	23.31	.68	
257.25	258.93	1.25✓	1.54✓	20.23	.59	
258.93	261.12	1.10✓	1.60✓	20.23	.59	
261.12	262.10	.80✓	.74✓	13.03	.38	
262.10	262.95	1.03✓	1.98✓	17.14	.50	
262.95	263.65	.68✓	.68✓	9.94	.29	
263.65	266.40	.93✓	.98✓	15.08	.44	
266.40	267.58	1.50✓	2.64✓	21.25	.62	
267.58	269.23	N/A	N/A	N/A	-	
269.23	270.72	2.10✓	3.06✓	34.28	1.00	
270.72	271.21	N/A	N/A	N/A	-	
271.21	272.80	1.88✓	3.42✓	23.31	.68	
272.80	275.05	N/A	N/A	N/A	-	
275.05	276.45	1.80✓	3.54✓	25.37	.74	
276.45	278.28	1.80✓	4.20✓	25.37	.74	
278.28	279.20	1.60✓	4.32✓	24.34	.71	
279.20	280.11	1.45✓	3.78✓	21.25	.62	
280.11	283.62	1.48✓	3.12✓	26.40	.77	
283.62	286.33	2.10✓	4.20✓	32.22	.94	
286.33	287.73	.85✓	.76✓	10.97	.32	
287.73	288.46	1.70✓	1.76✓	26.40	.77	
288.46	290.17	.30✓	.34✓	5.14	.15	
290.17	297.91 298.06	N/A	N/A	N/A	-	

HOLE NO: A-57

INTERVAL		ASSAYS			
FROM	TO	PB %	ZN %	AG GM/TON	AG OZ/TON
28.06 297.91	298.70	.09✓	.14✓	6.17	.18
298.70	299.10	1.83✓	4.26✓	34.28	1.00
299.10	302.88	.25✓	.32✓	8.23	.24
302.88	305.29	3.45✓	3.50	50.39	1.47
305.29	306.93	5.10✓	7.98✓	80.56	2.35
306.93	309.68	1.95✓	4.20✓	36.34	1.06
309.68	312.72	1.68✓	3.18✓	28.45	.83
312.72	314.86	1.33✓	2.94✓	22.28	.65
314.86	316.99	1.45✓	3.30✓	23.31	.68
316.99	318.67	2.78✓	6.48✓	49.36	1.44
318.67	320.04	1.68✓	6.72✓	30.17	.88
320.04	321.26	.59✓	.78✓	7.20	.21
321.26	326.84	N/A	N/A	N/A	.72
326.84	327.60	.23✓	.32✓	4.11	-
327.60	328.48	N/A	N/A	N/A	-
328.48	329.34	1.58✓	1.56✓	20.23	.59
329.34	388.47	N/A	N/A	N/A	-
388.47	389.84	.05✓	.21✓	1.03	.03
389.84	393.50	N/A	N/A	N/A	-
393.50	395.94	.02✓	.06✓	1.03	.03
395.94	416.36	N/A	N/A	N/A	-

MOORE SPECIFIC 4

HOLE NO: A-58 LATITUDE: 10618.08 AZIMUTH: 0.00
 HOLE LENGTH: 187.45 DEPARTURE: 7870.86 DIP: -90.00
 ELEVATION: 1293.25

DIP TESTS: DEPTH DIP AZIMUTH
 73.15 ✓ -87.00 ✓ 53.00 ✓
 121.92 ✓ -83.00 ✓ 54.00 ✓
~~170.69 -79.00 54.00~~

INTERVAL		ASSAYS				
FROM	TO	PB %	ZN %	AG GM/TON	AG OZ/TON	
0.00	133.05	N/A	N/A	N/A	-	
133.05	134.87	9.45 ✓	7.20 ✓	105.93	3.09	
134.87	136.70	4.73 ✓	6.60 ✓	70.62	2.06	
136.70	138.07	1.83 ✓	4.68 ✓	37.37	1.09	
138.07	138.99	4.05 ✓	7.08 ✓	80.56	2.35	
138.99	139.99	8.55 ✓	9.70 ✓	113.12	3.30	
139.99	140.82	6.38 ✓	8.93 ✓	83.64	2.44	
140.82	142.19	1.23 ✓	1.34 ✓	20.23	.59	
142.19	143.41	7.40 ✓	4.26 ✓	80.56	2.35	
143.41	144.29	1.58 ✓	.77 ✓	31.19	.91	
144.29	146.30	.37 ✓	.35 ✓	10.97	.32	
146.30	148.29	2.10 ✓	.91 ✓	28.45	.83	
148.29	150.88	.58 ✓	.71 ✓	13.03	.38	
150.88	153.01	.54 ✓	.59 ✓	15.08	.44	
153.01	155.14	.04 ✓	.02 ✓	6.17	.18	K
155.14	156.42	.03 ✓	.06 ✓	5.14	.15	
156.42	156.97	.04 ✓	.17 ✓	4.11	.12	
156.97	157.89	.03 ✓	.13 ✓	2.06	.06	
157.89	159.72	N/A	N/A	N/A	-	
159.72	160.63	.15 ✓	.03 ✓	5.14	.15	
160.63	163.98	.22 ✓	.46 ✓	4.11	.12	
163.98	165.81	.18 ✓	.25 ✓	1.03	.03	
165.81	187.45	N/A	N/A	N/A	-	


HOLE NO: A-59 LATITUDE: 11034.67 AZIMUTH: 0.00
HOLE LENGTH: 397.58 DEPARTURE: 7260.11 DIP: -90.00
ELEVATION: 1329.27

DIP TESTS:	DEPTH	DIP	AZIMUTH
✓ 60.96	-85.00	✓ 90.20	
✓ 121.92	-84.00	✓ 100.00	260.45-262.13 #923
✓ 182.88	-82.00	✓ 114.00	262.13-265.18 #924
✓ 243.84	-75.00	✓ 102.00	265.18-268.28 #925
✓ 304.80	-77.00	✓ 110.00	268.28-268.89 #926
✓ 365.76	-80.00	✓ 122.00	268.89-269.84 N/A

INTERVAL FROM	TO	PB %	ZN %	AG GM/TON	AG OZ/TON
0.00	258.74	N/A	N/A	N/A	-
258.74	260.45	5.93	11.11	90.84	2.65
260.45	269.84	N/A	N/A	N/A	-
269.84	271.67	1.65	3.18	25.37	.74
271.67	273.47	2.40	4.02	34.28	1.00
273.47	274.32	1.23	2.34	17.14	.50
274.32	280.08	N/A	N/A	N/A	-
280.08	283.25	.15	.28	3.09	.09
283.25	284.04	.85	1.36	13.03	.38
284.04	284.53	N/A	N/A	N/A	-
284.53	285.29	.73	1.24	12.00	.35
285.29	285.60	N/A	N/A	N/A	-
285.60	287.15	1.03	1.98	14.05	.41
287.15	288.58	.66	1.60	8.23	.24
288.58	290.29	.30	.44	4.11	.12
290.29	290.93	N/A	N/A	N/A	-
290.93	292.61	2.10	4.20	37.37	1.09
292.61	295.66	1.28	2.52	22.28	.65
295.66	298.76	1.88	3.96	30.17	.88
298.76	299.37	1.38	1.38	19.20	.56
299.37	308.52	N/A	N/A	N/A	-
308.52	310.44	.49	.94	7.20	.21
310.44	312.79	.44	1.00	7.20	.21
312.79	314.98	1.38	2.34	21.25	.62
314.98	316.23	.65	.95	9.94	.29
316.23	318.79	.65	1.24	9.94	.29
318.79	321.87	.65	1.14	9.94	.29
321.87	323.36	.63	.56	6.17	.18
323.36	324.73	.07	.09	1.03	.03
324.73	327.11	3.53	6.12	46.28	1.35
327.11	327.75	1.28	1.40	17.14	.50
327.75	329.67	.90	.45	20.23	.59
329.67	331.62	6.15	10.38	100.78	2.94
331.62	333.36	4.95	8.52	90.84	2.65
333.36	335.40	8.43	14.39	104.90	3.06
335.40	336.90	5.70	11.67	121.01	3.53
336.90	337.54	1.48	2.40	23.31	.68
337.54	337.84	.14	.72	6.17	.18
337.84	339.97	.19	.38	2.06	.06
339.97	340.31	9.65	16.21	201.57	5.88
340.31	341.01	.05	.18	6.17	.18
341.01	341.35	14.61	19.44	196.77	5.74

Results for
INTERVAL
260.45-269.84
#s 923
924
925
926

1.45



HOLE NO: A-59

INTERVAL		ASSAYS			AG
FROM	TO	PB %	ZN %	AG GM/TON	AG OZ/TON
341.35	343.14	.07✓	.12✓	2.06	.06
343.14	344.45	11.00✓	17.19✓	176.54	5.15
344.45	380.45	N/A	N/A	N/A	-
380.45	381.70	2.33✓	2.52✓	53.13	1.55
381.70	382.86	3.30✓	4.62✓	68.56	2.00
382.86	384.11	N/A	N/A	N/A	-
384.11	384.41	4.50✓	8.16✓	43.54	1.27
384.41	384.66	N/A	N/A	N/A	-
384.66	387.25	5.10✓	8.28✓	73.70	2.15
387.25	387.64	.68✓	.40✓	8.23	.24
387.64	389.75	6.30✓	9.41✓	100.78	2.94
389.75	390.91	5.70✓	8.52✓	100.78	2.94
390.91	392.40	5.70✓	8.64✓	80.56	2.35
392.40	393.62	2.10✓	1.84✓	44.22	1.29
393.62	397.58	N/A	N/A	N/A	-

HOLE NO: A-60 LATITUDE: 10656.40 AZIMUTH: 0.00 ✓
 HOLE LENGTH: 361.49 DEPARTURE: 7568.59 DIP: -90.00 ✓
 ELEVATION: 1289.47

DIP TESTS: DEPTH DIP AZIMUTH
 79.25 ✓ -85.00 ✓ 78.50 ✓
 126.49 ✓ -82.00 ✓ 75.50 ✓
 193.55 ✓ -80.00 ✓ 77.50 ✓
 217.93 ✓ -79.00 ✓ 65.50 ✓

*+ ropari
 can't check.*

INTERVAL		ASSAYS			AG
FROM	TO	PB	ZN	AG	AG
		%	%	GM/TON	02/TON
0.00	99.97	N/A	N/A	N/A	-
99.97	100.80	.28 ✓	.24 ✓	4.11	.12
100.80	102.35	5.18 ✓	7.08 ✓	78.50	2.29
102.35	103.33	7.50 ✓	9.71 ✓	123.07	3.59
103.33	104.03	3.53 ✓	3.78 ✓	75.76	2.21
104.03	105.46	.09 ✓	.12 ✓	3.09	.09
105.46	106.34	.15 ✓	.15 ✓	4.11	.12
106.34	107.23	1.60 ✓	.54 ✓	29.14	.85
107.23	109.42	7.35 ✓	8.76 ✓	112.10	3.27
109.42	110.83	7.28 ✓	7.56 ✓	111.07	3.24
110.83	111.47	.24 ✓	.25 ✓	4.11	.12
111.47	114.00	3.68 ✓	3.18 ✓	43.54	1.27
114.00	116.13	5.18 ✓	5.04 ✓	80.56	2.35
116.13	116.65	.68 ✓	.51 ✓	19.20	.56
116.65	123.72	N/A	N/A	N/A	-
123.72	124.66	.19 ✓	.11 ✓	2.06	.06
124.66	125.94	.84 ✓	.77 ✓	13.03	.38
125.94	127.28	N/A	N/A	N/A	-
127.28	128.32	.78 ✓	.85 ✓	9.94	.29
128.32	132.37	N/A	N/A	N/A	-
132.37	133.41	2.78 ✓	2.82 ✓	49.36	1.44
133.41	135.45	5.55 ✓	4.74 ✓	64.45	1.88
135.45	137.01	4.73 ✓	4.80 ✓	54.51	1.59
137.01	137.53	.69 ✓	.99 ✓	7.20	.21
137.53	145.88	N/A	N/A	N/A	-
145.88	147.13	11.48 ✓	17.35 ✓	171.40	5.00
147.13	179.95	N/A	N/A	N/A	-
179.95	180.59	1.55 ✓	1.86 ✓	19.20	.56
180.59	183.03	N/A	N/A	N/A	-
183.03	183.67	1.13 ✓	1.02 ✓	20.23	.59
183.67	259.69	N/A	N/A	N/A	-
259.69	262.13	.07 ✓	.04 ✓	.00	TR
262.13	267.00	N/A	N/A	N/A	-
267.00	268.53	.10 ✓	.36 ✓	1.03	.03
268.53	274.32	N/A	N/A	N/A	-
274.32	276.33	.02 ✓	.03 ✓	.00	TR
276.33	286.21	N/A	N/A	N/A	-
286.21	287.33	1.30 ✓	1.14 ✓	16.11	.47
287.33	322.48	N/A	N/A	N/A	-
322.48	323.55	.39 ✓	.51 ✓	8.23	.24
323.55	325.68	2.93 ✓	2.70 ✓	39.42	1.15
325.68	326.53	1.00 ✓	.85 ✓	15.08	.44
326.53	328.45	.63 ✓	.32 ✓	9.94	.29
328.45	330.07	3.68 ✓	2.88 ✓	44.22	1.29

SPECIFIC MODEL BUSINESS FORMS 4

HOLE NO: A-60

INTERVAL		ASSAYS				
FROM	TO	PB %	ZN %	AG GM/TON	AG 02/TON	
330.07	331.59	1.28 ✓	.74 ✓	25.37	.74	K
331.59	335.28	.25 ✓	.25 ✓	7.20	.21	
335.28	339.67	N/A	N/A	N/A	-	
339.67	341.10	1.63 ✓	.66 ✓	27.42	.80	
341.10	345.06	N/A	N/A	N/A	-	
345.06	347.81	.08 ✓	.03 ✓	3.09	.09	
347.81	361.49	N/A	N/A	N/A	-	

SPEEDULO MOORE BUSINESS FORMS 4

HOLE NO: A-61 LATITUDE: 11080.86 ✓ AZIMUTH: 0.00
 HOLE LENGTH: 276.45 DEPARTURE: 7302.55 DIP: -90.00
 ELEVATION: 1328.93

DIP TESTS:	DEPTH	DIP	AZIMUTH
	60.96	-83.30	108.10
	121.92	-80.00	117.30
	182.88	-77.00	137.00
	243.80	-74.00	137.00

INTERVAL		ASSAYS				AG
FROM	TO	PB	ZN	AG		AG
		%	%	GM/TON		OZ/TON
0.00	240.55	N/A	N/A	N/A		-
240.55	242.19	.39 ✓	.72 ✓	6.17		.18
242.19	243.23	1.40 ✓	2.46 ✓	17.14		.50
243.23	244.11	1.93 ✓	4.02 ✓	40.45		1.18
244.11	245.27	1.05 ✓	1.66 ✓	10.97		.32
245.27	256.03	N/A	N/A	N/A		-
256.03	257.56	1.88 ✓	2.64 ✓	35.31		1.03
257.56	264.14	N/A	N/A	N/A		-
264.14	265.79	1.55 ✓	1.88 ✓	22.28		.65
265.79	268.56	1.85 ✓	3.00 ✓	32.57		.95
268.56	271.61	1.50 ✓	1.72 ✓	22.28		.65
271.61	273.47	1.28 ✓	1.76 ✓	19.20		.56
273.47	276.45	1.10 ✓	1.54 ✓	15.08		.44

HOLE NO: A-62 LATITUDE: 10660.22 AZIMUTH: 0.00
 HOLE LENGTH: 301.14 DEPARTURE: 7650.77 DIP: -90.00
 ELEVATION: 1290.45

DIP TESTS:	DEPTH	DIP	AZIMUTH
	61.00 ✓	-86.30 ✓	121.20 ✓
	121.90 ✓	-80.00 ✓	105.20 ✓
	182.90 ✓	-79.00 ✓	113.20 ✓
	225.60 ✓	-73.00 ✓	100.20 ✓

INTERVAL		ASSAYS			AG OZ/TON
FROM	TO	PB %	ZN %	AG GM/TON	
0.00	48.16	N/A	N/A	N/A	-
48.16	52.12	.33 ✓	.18 ✓	9.94	.29
52.12	74.37	N/A	N/A	N/A	-
74.37	75.59	2.10 ✓	2.40 ✓	29.14	.85
75.59	76.50	11.13 ✓	9.51 ✓	153.23	4.47
76.50	81.38	N/A	N/A	N/A	-
81.38	82.45	7.53 ✓	6.48 ✓	92.90	2.71
82.45	84.43	9.93 ✓	6.24 ✓	114.84	3.35
84.43	85.53	.62 ✓	.78 ✓	8.91	.26
85.53	126.64	N/A	N/A	N/A	-
126.64	128.63	6.68 ✓	11.05 ✓	105.93	3.09
128.63	130.45	5.60 ✓	10.25 ✓	85.70	2.50
130.45	131.77	.18 ✓	.62 ✓	8.57	.25
131.77	132.95	2.78 ✓	5.88 ✓	50.39	1.47
132.95	134.63	4.65 ✓	8.94 ✓	84.67	2.47
134.63	136.31	4.80 ✓	10.16 ✓	92.90	2.71
136.31	138.17	5.94 ✓	11.82 ✓	103.87	3.03
138.17	166.02	N/A	N/A	N/A	-
166.02	167.03	1.12 ✓	1.14 ✓	12.00	.35
167.03	176.05	N/A	N/A	N/A	-
176.05	177.45	3.08 ✓	4.26 ✓	45.25	1.32
177.45	178.92	.18 ✓	.45 ✓	19.20	.56
178.92	181.66	.27 ✓	.72 ✓	10.97	.32
181.66	183.18	.49 ✓	.80 ✓	12.00	.35
183.18	186.23	.27 ✓	1.30 ✓	9.94	.29
186.23	198.61	N/A	N/A	N/A	-
198.61	201.17	.53 ✓	.76 ✓	8.91	.26
201.17	218.15	N/A	N/A	N/A	-
218.15	220.77	1.43 ✓	1.36 ✓	15.08	.44
220.77	245.24	N/A	N/A	N/A	-
245.24	246.46	3.75 ✓	4.50 ✓	32.22	.94
246.46	247.95	.04 ✓	.14 ✓	1.03	.03
247.95	248.72	.48 ✓	.72 ✓	2.06	.06
248.72	251.76	N/A	N/A	N/A	-
251.76	252.95	.10 ✓	.14 ✓	1.03	.03
252.95	254.87	3.08 ✓	4.02 ✓	45.25	1.32
254.87	256.31	.68 ✓	1.12 ✓	10.97	.32
256.31	258.74	1.98 ✓	1.36 ✓	30.17	.88
258.74	260.66	5.55 ✓	6.24 ✓	76.79	2.24
260.66	262.13	1.95 ✓	2.46 ✓	32.22	.94
262.13	267.00	N/A	N/A	N/A	-
267.00	269.02	.68 ✓	.78 ✓	13.03	.38
269.02	295.26	N/A	N/A	N/A	-
295.26	296.36	.23 ✓	.24 ✓	8.23	.29

SPECIAL TO MOORE BUSINESS FORMS 4

STER FILE

HOLE NO: A-62

INTERVAL		ASSAYS			AG	
FROM	TO	PB %	ZN %	AG GM/TON	AG OZ/TON	
296.36	298.00	.50	1.38	35.31	1.03	← 2.50
298.00	298.89	.27	.62	8.23	.24	
298.89	301.14	N/A	N/A	N/A	-	

HOLE NO: A-63 LATITUDE: 10314.44 AZIMUTH: 0.00
 HOLE LENGTH: 180.14 DEPARTURE: 7744.20 DIP: -90.00
 ELEVATION: 1271.27

INTERVAL		ASSAYS				AG
FROM	TO	PB	ZN	AG		
		%	%	GM/TON		02/TON
0.00	78.64	N/A	N/A	N/A		-
78.64	79.86	1.73✓	1.48✓	26.40		.77
79.86	80.77	1.40✓	1.02✓	25.37		.74
80.77	81.53	2.15✓	2.64✓	30.17		.88
81.53	83.21	3.15✓	1.90✓	41.48		1.21
83.21	86.26	.37✓	.32✓	9.94		.29
86.26	89.31	.15✓	.12✓	5.14		.15
89.31	90.22	.37✓	.29✓	15.08		.44
90.22	93.27	.18✓	.15✓	5.14		.15
93.27	96.01	.14✓	.27✓	5.14		.15
96.01	96.62	.10✓	.38✓	3.43		.10
96.62	98.45	.50✓	1.10✓	9.94		.29
98.45	99.06	.47✓	1.38✓	8.91		.26
99.06	99.49	5.63✓	7.20✓	62.39		1.82
99.49	100.04	.05✓	.48✓	2.06		.06
100.04	102.63	5.70✓	7.90✓	73.70		2.15
102.63	104.70	4.13✓	6.72✓	69.59		2.03
104.70	106.22	4.43✓	6.96✓	65.47		1.91
106.22	107.75	4.58✓	6.48✓	68.56		2.00
107.75	108.66	1.68✓	2.00✓	28.45		.83
108.66	110.95	5.33✓	8.95✓	71.65		2.09
110.95	111.86	.87✓	1.60✓	9.94		.29
111.86	112.65	4.58✓	7.56✓	58.62		1.71
112.65	113.08	N/A	N/A	N/A		-
113.08	114.00	1.93✓	3.42✓	27.42		.80
114.00	114.60	N/A	N/A	N/A		-
114.60	117.35	.20✓	.40✓	6.17		.18
117.35	119.33	.15✓	.55✓	5.14		.15
119.33	121.31	1.23✓	2.46✓	20.23		.59
121.31	122.38	.27✓	.69✓	8.23		.24
122.38	124.66	.10✓	.29✓	3.43		.10
124.66	127.71	.09✓	.31✓	1.37		.04
127.71	129.84	.08✓	.23✓	1.03		.03
129.84	132.22	4.50✓	6.24✓	58.62		1.71
132.22	133.65	1.40✓	1.78✓	17.14		.50
133.65	145.39	N/A	N/A	N/A		-
145.39	146.00	.44✓	.75✓	6.17		.18
146.00	147.92	2.15✓	2.22✓	25.37		.74
147.92	150.88	.15✓	.17✓	5.14		.15
150.88	153.92	.27✓	.39✓	6.86		.20
153.92	156.58	2.20	2.40	33.25		
156.58	159.11	.13	.22	3.43		
159.11	161.67	1.88	1.66	26.40		
161.67	163.40	1.10	1.40	20.23		
163.40	164.90	1.65	1.62	25.37		
164.90	166.54	1.85	1.56	28.45		
166.54	167.37	.23	.25	6.17		
167.37	168.46	4.65	5.22	55.53		
168.46	169.38	.12	.13	3.43		
169.38	171.91	1.70	2.58	23.31		

SPEED TO MOORE BUSINESS FORMS

HOLE NO: A-63

INTERVAL		ASSAYS		
FROM	TO	PB %	ZN %	AG GM/TON
171.91	173.22	.17	.40	5.14
173.22	176.17	.05	.10	1.37
176.17	177.73	.07	.12	2.06
177.73	180.14	N/A	N/A	N/A

HOLE NO: A-64 LATITUDE: 11589.36 AZIMUTH: 0.00
 HOLE LENGTH: 432.21 DEPARTURE: 6945.43 DIP: -90.00
 ELEVATION: 1305.76

DIP TESTS:	DEPTH	DIP	AZIMUTH
	60.96✓	-86.00✓	152.20✓
	121.92✓	-81.30✓	152.20✓
	182.88✓	-73.25✓	136.50✓
	243.80✓	-63.30✓	144.20✓
	304.80✓	-66.00✓	134.20✓
	350.52✓	-71.30✓	142.20✓

INTERVAL		ASSAYS				AG
FROM	TO	PB	ZN	AG		02/TON
		%	%	GM/TON		
0.00	320.80	N/A	N/A	N/A		-
320.80	322.17	.85✓	1.68✓	7.20		.21
322.17	322.87	N/A	N/A	N/A		-
322.87	324.92	1.13✓	1.80✓	15.08		.44
324.92	369.11	N/A	N/A	N/A		-
369.11	372.16	1.10✓	2.34✓	15.08		.44
372.16	385.63	N/A	N/A	N/A		-
385.63	387.10	1.43✓	2.58✓	15.08		.44
387.10	389.23	1.33✓	2.40✓	15.08		.44
389.23	390.91	N/A	N/A	N/A		-
390.91	392.73	1.70✓	2.88✓	18.17		.53
392.73	394.26	2.50✓	6.42✓	29.14		.85
394.26	395.78	3.60✓	8.77✓	51.42		1.50
395.78	397.31	2.13✓	5.25✓	39.42		1.15
397.31	398.83	1.63✓	4.80✓	25.37		.74
398.83	432.21	N/A	N/A	N/A		-

SPECIAL MOORE BUSINESS FORMS 4

HOLE NO: A-65 LATITUDE: 10742.70 AZIMUTH: 0.00
 HOLE LENGTH: 167.64 DEPARTURE: 7559.77 DIP: -90.00
 ELEVATION: 1299.30

DIP TESTS: DEPTH DIP AZIMUTH
 167.64 ✓ -85.00 ✓ 158.00 ✓ *tropari*

INTERVAL		ASSAYS				
FROM	TO	PB	ZN	AG	AG	
		%	%	GM/TON	02/TON	
0.00	123.75	N/A	N/A	N/A	-	
123.75	125.58	1.43 ✓	1.52 ✓	18.17	.53	
125.58	126.49	10.50 ✓	10.11	115.87	3.38	
126.49	128.02	6.00 ✓	5.64 ✓	74.73	2.18	
128.02	128.93	4.80 ✓	2.46 ✓	58.62	1.71	
128.93	130.45	8.42 ✓	5.40 ✓	94.61	2.76	
130.45	132.16	6.53 ✓	3.78	84.67	2.47	
132.16	153.92	N/A	N/A	N/A	-	
153.92	154.20	.20 ✓	.60 ✓	2.06	.06	
154.20	155.97	8.70 ✓	13.84 ✓	145.00	4.23	
155.97	157.28	8.10	8.20 ✓	114.84	3.35	
157.28	159.99	4.43 ✓	7.65 ✓	63.42	1.85	
159.99	161.54	.22 ✓	.37 ✓	5.14	.15	
161.54	164.29	.57 ✓	.69 ✓	15.08	.44	
164.29	165.20	3.75 ✓	1.56 ✓	37.37	1.09	
165.20	167.64	4.20 ✓	1.54 ✓	40.45	1.18	

SPECIFIC MOORE BUSINESS FORMS 4

HOLE NO: A-66
 HOLE LENGTH: 182.88

LATITUDE: 10575.39
 DEPARTURE: 7741.44
 ELEVATION: 1287.53

AZIMUTH: 0.00
 DIP: -90.00

DIP TESTS: DEPTH DIP AZIMUTH
 57.91 ✓ -88.00 ✓ 110.00 ✓
 115.82 ✓ -88.00 ✓ 94.00 ✓ *tropari*
 176.78 ✓ -80.00 ✓ 103.30 ✓

INTERVAL FROM	TO	ASSAYS			AG GM/TON	AG OZ/TON
		PB %	ZN %	AG GM/TON		
0.00	51.21	N/A	N/A	N/A	-	
51.21	53.04	1.58 ✓	2.34 ✓	28.11	.82	
53.04	53.95	1.10 ✓	1.82 ✓	15.08	.44	
53.95	61.57	N/A	N/A	N/A	-	
61.57	63.46	.84 ✓	1.84 ✓	14.05	.41	
63.46	64.31	N/A	N/A	N/A	-	
64.31	66.45	2.23 ✓	3.36 ✓	38.39	1.12	
66.45	68.28	1.53 ✓	3.18 ✓	23.31	.68	
68.28	70.01	2.10 ✓	4.44 ✓	23.31	.68	
70.01	81.69	N/A	N/A	N/A	-	
81.69	84.12	5.40 ✓	10.80 ✓	66.50	1.94	
84.12	85.74	8.84 ✓	14.83 ✓	105.93	3.09	
85.74	86.56	5.10 ✓	5.76 ✓	61.02	60.33 1.76	
86.56	88.57	5.48 ✓	4.98 ✓	63.42	1.85	
88.57	89.46	5.63 ✓	5.52 ✓	61.36	1.79	
89.46	90.22	.40 ✓	.82 ✓	9.94	.29	
90.22	93.27	.28 ✓	1.07 ✓	8.23	.24	
93.27	95.10	.56 ✓	.95 ✓	10.97	.32	
95.10	97.08	.95 ✓	.96 ✓	20.23	.59	
97.08	100.13	.49 ✓	3.12 ✓	8.23	.24	
100.13	103.02	.21 ✓	.42 ✓	5.14	.15	
103.02	103.63	.30 ✓	1.08 ✓	9.94	.29	
103.63	106.07	4.55 ✓	6.00 ✓	58.62	1.71	
106.07	107.20	4.65 ✓	5.82 ✓	52.45	1.53	
107.20	107.81	.15 ✓	.96 ✓	5.14	.15	
107.81	113.69	.00 ^{N/A}	.00 ^{N/A}	.00 ^{N/A}	-	
113.69	115.21	.44 ✓	.77 ✓	8.91	.26	
115.21	118.26	N/A	N/A	N/A	-	
118.26	119.66	2.25 ✓	1.22 ✓	37.37	1.09	
119.66	129.69	N/A	N/A	N/A	-	
129.69	131.86	.28 ✓	.78 ✓	8.23	.24	
131.86	138.68	N/A	N/A	N/A	-	
138.68	140.21	.03 ✓	4.20 ✓	1.03	.03	
140.21	143.26	N/A	N/A	N/A	-	
143.26	144.78	.04 ✓	.09 ✓	2.06	.06	
144.78	155.45	N/A	N/A	N/A	-	
155.45	156.36	8.56 ✓	10.15 ✓	130.95	3.82	
156.36	158.19	1.75 ✓	3.00 ✓	25.37	.74	
158.19	160.02	5.70 ✓	7.20 ✓	72.67	2.12	
160.02	161.97	N/A	N/A	N/A	-	
161.97	162.89	2.00 ✓	1.66 ✓	30.17	.88	
162.89	182.88	N/A	N/A	N/A	-	

SPECIAL LO MOORE BUSINESS FORMS 4

HOLE NO: A-67 LATITUDE: 10913.48 AZIMUTH: 0.00
 HOLE LENGTH: 406.62 DEPARTURE: 7561.88 DIP: -90.00
 ELEVATION: 1313.90

DIP TESTS: DEPTH DIP AZIMUTH
 122.53 ✓ -86.00 ✓ 340.00 ✓
 244.45 ✓ -85.00 ✓ 96.00 ✓ *tropari*
 378.56 ✓ -85.00 ✓ 103.00 ✓

INTERVAL		ASSAYS				
FROM	TO	PB %	ZN %	AG GM/TON	AG 02/TON	
0.00	139.29	N/A	N/A	N/A	-	
139.29	142.04	8.52 ✓	14.11 ✓	126.15	3.68	
142.04	144.17	2.05 ✓	4.50	30.17	.88	
144.17	146.36	.57 ✓	.60 ✓	5.14	.15	
146.36	147.58	1.80 ✓	1.48 ✓	20.23	.59	
147.58	149.99	1.50 ✓	1.84 ✓	16.11	.47	
149.99	152.10	1.14 ✓	3.30 ✓	20.23	.59	
152.10	153.31	5.25 ✓	7.40 ✓	65.47	1.91	
153.31	155.30	2.93 ✓	3.84 ✓	39.42	1.15	
155.30	161.45	N/A	N/A	N/A	-	
161.45	163.22	1.04 ✓	1.74 ✓	15.08	.44	
163.22	166.42	N/A	N/A	N/A	-	
166.42	168.43	2.13 ✓	3.84 ✓	34.28	1.00	
168.43	173.64	N/A	N/A	N/A	-	
173.64	176.17	1.95 ✓	2.97 ✓	30.17	.88	
176.17	178.92	1.75 ✓	2.76 ✓	26.05	.76	
178.92	180.75	1.55 ✓	2.34 ✓	17.14	.50	
180.75	182.79	1.50 ✓	2.34 ✓	21.25	.62	
182.79	184.89	2.33 ✓	3.90 ✓	34.28	1.00	
184.89	186.48	2.38 ✓	3.30 ✓	36.34	1.06	
186.48	189.01	2.18 ✓	4.26 ✓	33.25	.97	
189.01	190.26	1.25 ✓	3.06 ✓	17.14	.50	
190.26	192.39	.55 ✓	1.40 ✓	6.17	.18	
192.39	194.16	2.13 ✓	4.92 ✓	30.17	.88	
194.16	195.99	2.15 ✓	4.62 ✓	35.31	1.03	
195.99	197.51	1.73 ✓	4.08 ✓	34.28	1.00	
197.51	199.34	1.63 ✓	4.08 ✓	37.37	1.09	
199.34	200.68	1.73 ✓	3.66 ✓	39.42	1.15	
200.68	201.69	2.78 ✓	5.82 ✓	55.53	1.62	
201.69	204.34	4.05 ✓	9.05 ✓	72.67	2.12	
204.34	205.74	N/A	N/A	N/A	-	
205.74	208.27	4.35 ✓	5.58 ✓	62.39	1.82	
208.27	210.01	3.90 ✓	7.99 ✓	55.53	1.62	
210.01	211.74	N/A	N/A	N/A	-	
211.74	213.91	2.13 ✓	4.26 ✓	32.22	.94	
213.91	229.21	N/A	N/A	N/A	-	
229.21	230.34	6.90 ✓	9.32 ✓	124.09	3.62	
230.34	237.74	N/A	N/A	N/A	-	
237.74	240.06	6.90 ✓	10.18 ✓	125.12	3.65	
240.06	243.41	N/A	N/A	N/A	-	
243.41	243.93	3.98 ✓	4.02 ✓	50.39	1.47	
243.93	245.67	N/A	N/A	N/A	-	
245.67	247.47	1.10 ✓	1.52 ✓	15.08	.44	
247.47	277.98	N/A	N/A	N/A	-	
277.98	280.81	1.10 ✓	1.83 ✓	10.97	.32	

SHEETS TO MOORE BUSINESS FORMS 4

HOLE NO: A-67

INTERVAL		ASSAYS			
FROM	TO	PB %	ZN %	AG GM/TON	AG OZ/TON
280.81	283.16	N/A	N/A	N/A	-
283.16	284.07	.80✓	.43✓	8.91	.26
284.07	285.05	4.13✓	5.88✓	60.33	1.76
285.05	287.49	5.55✓	7.72✓	83.64	2.44
287.49	289.10	1.22✓	1.08✓	17.14	.50
289.10	307.54	N/A	N/A	N/A	-
307.54	310.29	.68✓	.62✓	12.00	.35
310.29	311.51	.57✓	1.27✓	9.94	.29
311.51	320.04	N/A	N/A	N/A	-
320.04	321.02	.48✓	.78✓	8.91	.26
321.02	323.97	1.65✓	1.92✓	20.23	.59
323.97	324.79	.40✓	.62✓	8.91	.26
324.79	340.16	N/A	N/A	N/A	-
340.16	341.32	1.33✓	2.88✓	20.23	.59
341.32	343.24	2.23✓	3.78✓	39.42	1.15
343.24	344.91	1.15✓	1.62✓	18.17	.53
344.91	346.89	N/A	N/A	N/A	-
346.89	347.87	3.60✓	4.38✓	50.39	1.47
347.87	349.33	N/A	N/A	N/A	-
349.33	351.43	5.33✓	7.57✓	85.70	2.50
351.43	352.75	3.38✓	1.74✓	34.28	1.00
352.75	353.96	3.75✓	.59✓	28.11	.82
353.96	354.97	2.05✓	2.64✓	37.37	1.09
354.97	406.60	N/A	N/A	N/A	-

SPEER LO MOORE BUSINESS FORMS 4

HOLE NO: A-68 LATITUDE: 10870.22 AZIMUTH: 0.00
 HOLE LENGTH: 389.23 DEPARTURE: 7607.27 DIP: -90.00
 ELEVATION: 1314.71

DIP TESTS: DEPTH DIP AZIMUTH
 121.92✓ -77.00✓ ~~119.00~~✓
 237.74✓ -83.30✓ ~~119.00~~✓
 389.23✓ -83.00✓ 119.00✓

INTERVAL		ASSAYS				AG
FROM	TO	PB %	ZN %	AG GM/TON	AG OZ/TON	
0.00	128.47	N/A	N/A	N/A	-	
128.47	129.75	7.71✓	12.62✓	105.93	3.09	
129.75	130.45	2.38✓	4.08✓	28.45	.83	
130.45	132.19	1.13✓	2.64✓	15.08	.44	
132.19	133.20	2.93✓	5.64✓	40.45	1.18	
133.20	135.94	1.60✓	2.88✓	20.23	.59	
135.94	137.40	3.98✓	3.12✓	35.31	1.03	
137.40	139.17	3.60✓	2.40✓	28.45	.83	
139.17	141.85	1.68✓	2.46✓	22.28	.65	
141.85	143.99	.98✓	1.64✓	15.08	.44	
143.99	144.78	3.15✓	4.92✓	45.25	1.32	
144.78	147.31	4.20✓	8.20✓	60.33	1.76	
147.31	156.97	N/A	N/A	N/A	-	
156.97	158.50	1.78✓	3.12✓	26.40	.77	
158.50	160.02	N/A	N/A	N/A	-	
160.02	161.24	1.58✓	2.88✓	25.37	.74	
161.24	163.98	1.80✓	1.80✓	28.45	.83	
163.98	165.81	1.30✓	1.20✓	19.20	.56	
165.81	168.86	1.55✓	3.06✓	26.40	.77	
168.86	170.08	1.35✓	2.58✓	16.11	.47	
170.08	173.43	2.45✓	4.56✓	40.45	1.18	
173.43	176.30	2.45✓	4.56✓	40.45	1.18	
176.30	179.47	1.93✓	3.78✓	29.14	.85	
179.47	181.57	1.33✓	3.78✓	22.28	.65	
181.57	183.67	1.70✓	2.88✓	35.31	1.03	
183.67	185.32	2.13✓	4.92✓	44.22	1.29	
185.32	187.36	4.28✓	5.22✓	62.39	1.82	
187.36	188.70	3.38✓	1.76✓	32.22	.94	
188.70	190.20	3.30✓	4.80✓	40.45	1.18	
190.20	192.88	5.45✓	9.85✓	81.59	2.38	
192.88	193.43	1.10✓	3.00✓	20.23	.59	
193.43	199.92	N/A	N/A	N/A	-	
199.92	201.66	4.50✓	4.26✓	55.53	1.62	
201.66	203.51	.53✓	1.18✓	9.94	.29	
203.51	205.22	8.00✓	7.80✓	110.04	3.21	
205.22	206.84	8.15✓	15.38✓	121.01	3.53	
206.84	207.97	3.30✓	5.22✓	64.45	1.88	
207.97	208.79	.62✓	.50✓	7.20	.21	
208.79	209.70	4.65✓	4.32✓	55.53	1.62	
209.70	210.37	N/A	N/A	N/A	-	
210.37	212.14	2.00✓	1.84✓	30.17	.88	
212.14	213.76	1.73✓	2.52✓	37.37	1.09	
213.76	215.28	1.18✓	3.18✓	25.37	.74	
215.28	217.44	7.63✓	9.81✓	102.84	3.00	
217.44	219.27	10.23✓	19.00✓	141.23	4.12	

SHEED TO MOORE BUSINESS FORMS 4

HOLE NO: A-68

INTERVAL		ASSAYS			
FROM	TO	PB %	ZN %	AG GM/TON	AG OZ/TON
219.27	219.91	10.06 ✓	12.46 ✓	121.01	3.53
219.91	222.47	N/A	N/A	N/A	-
222.47	225.37	5.30 ✓	6.84 ✓	75.76	2.21
225.37	240.18	N/A	N/A	N/A	-
240.18	241.04	.40 ✓	1.00 ✓	4.11	1.70
241.04	242.38	4.73 ✓	6.00 ✓	75.76	2.21
242.38	243.99	5.10 ✓	8.30 ✓	70.62	2.06
243.99	244.75	.30 ✓	.34 ✓	6.17	.18
244.75	246.46	3.23 ✓	3.72 ✓	34.28	1.00
246.46	247.38	.23 ✓	.35 ✓	5.14	.15
247.38	249.51	5.63 ✓	10.47 ✓	75.76	2.21
249.51	250.48	1.14 ✓	1.33 ✓	15.08	.44
250.48	297.67	N/A	N/A	N/A	-
297.67	299.01	.15 ✓	.40 ✓	5.14	.15
299.01	301.45	2.40 ✓	2.70 ✓	25.02	.73
301.45	302.61	.02 ✓	.03 ✓	1.03	.03
302.61	304.77	2.63 ✓	2.40 ✓	22.28	.65
304.77	323.33	N/A	N/A	N/A	-
323.33	324.92	1.21 ✓	2.70 ✓	20.23	.59
324.92	330.40	N/A	N/A	N/A	-
330.40	332.54	5.60 ✓	7.75 ✓	83.64	2.44
332.54	334.58	4.50 ✓	6.32 ✓	68.56	2.00
334.58	335.65	2.24 ✓	2.70 ✓	30.17	.88
335.65	337.11	.14 ✓	.19 ✓	2.06	.06
337.11	340.16	.25 ✓	.33 ✓	4.11	.12
340.16	389.23	N/A	N/A	N/A	-

SPRINT/LO MOORE BUSINESS FORMS 4

HOLE NO: A-69 LATITUDE: 10955.31 AZIMUTH: 0.00
HOLE LENGTH: 410.26 DEPARTURE: 7517.40 DIP: -90.00
ELEVATION: 1313.14

DIP TESTS: DEPTH DIP AZIMUTH
122.53 ✓ -82.00 ✓ 133.00 ✓
244.45 ✓ -86.00 ✓ 133.00 ✓ *tropari*
366.37 ✓ -85.00 ✓ 172.00 ✓

INTERVAL		ASSAYS				
FROM	TO	PB %	ZN %	AG GM/TON	AG OZ/TON	
0.00	137.77	N/A	N/A	N/A	-	
137.77	138.56	6.31 ✓	8.39 ✓	91.87	2.68	
138.56	140.18	.40 ✓	.39 ✓	9.94	.29	
140.18	140.94	6.48 ✓	5.04 ✓	95.64	2.79	
140.94	143.16	.27 ✓	.33 ✓	6.17	.18	
143.16	143.80	6.76 ✓	9.39 ✓	91.87	2.68	
143.80	144.29	N/A	N/A	N/A	-	
144.29	146.61	4.73 ✓	6.72 ✓	66.50	1.94	
146.61	147.83	3.90 ✓	7.40 ✓	56.56	1.65	
147.83	149.35	1.08 ✓	1.84 ✓	20.23	.59	
149.35	150.91	2.45 ✓	4.08 ✓	35.31	1.03	
150.91	151.30	1.40 ✓	3.48 ✓	23.31	.68	
151.30	156.51	N/A	N/A	N/A	-	
156.51	158.80	.79 ✓	1.84 ✓	10.97	.32	
158.80	160.84	2.03 ✓	2.88 ✓	27.08	.79	
160.84	162.31	2.43 ✓	4.62 ✓	35.31	1.03	
162.31	164.59	1.02 ✓	1.68 ✓	18.17	.53	
164.59	168.07	.20 ✓	.48 ✓	2.06	.06	
168.07	169.74	2.05 ✓	4.56 ✓	27.08	.79	
169.74	170.32	.59 ✓	1.44 ✓	7.20	.21	
170.32	172.15	N/A	N/A	N/A	-	
172.15	172.46	.72 ✓	1.54 ✓	6.17	.18	
172.46	175.26	2.15	3.48	30.17	.88	
175.26	177.24	N/A 1.44	N/A 1.64	N/A 21.25	-	sample 1374 .62
177.24	179.25	2.23 ✓	4.62 ✓	35.31	1.03	
179.25	180.75	1.63 ✓	3.84 ✓	27.08	.79	
180.75	182.48	2.28 ✓	3.66 ✓	34.28	1.00	
182.48	185.62	1.47 ✓	2.61 ✓	20.23	.59	
185.62	186.75	.40 ✓	.92 ✓	3.09	.09	
186.75	187.76	1.68 ✓	2.58 ✓	24.34	.71	
187.76	189.59	2.10 ✓	4.26 ✓	28.11	.82	
189.59	190.80	3.00 ✓	4.74 ✓	36.34	1.06	
190.80	191.51	1.18 ✓	2.40 ✓	14.05	.41	
191.51	192.63	.58 ✓	1.38 ✓	7.20	.21	
192.63	194.52	1.28 ✓	1.62 ✓	15.08	.44	
194.52	196.14	1.45 ✓	2.76 ✓	20.23	.59	
196.14	198.27	2.05 ✓	4.08 ✓	30.17	.88	
198.27	200.56	1.58 ✓	2.94 ✓	25.37	.74	
200.56	202.69	1.63 ✓	4.08 ✓	24.34	.71	
202.69	204.52	1.63 ✓	3.60 ✓	5.48	.16	
204.52	206.08	.69 ✓	1.50 ✓	20.23	.59	
206.08	207.29	1.30 ✓	3.12 ✓	29.14	.85	
207.29	209.25	2.30 ✓	5.58 ✓	44.22	1.29	
209.25	210.92	.63 ✓	.74 ✓	13.03	.38	
210.92	213.24	5.10 ✓	8.28 ✓	80.56	2.35	



SPECIAL TO MOORE BUSINESS FORMS 4

HOLE NO: A-69

INTERVAL		ASSAYS			
FROM	TO	PB %	ZN %	AG GM/TON	AG OZ/TON
213.24	213.97	6.55✓	11.05✓	95.64	2.79
213.97	215.13	.47✓	.30✓	9.94	.29
215.13	215.89	1.35✓	1.90✓	26.05	.76
215.89	217.08	.17✓	.21✓	4.11	.12
217.08	217.72	1.78✓	6.42✓	27.08	.79
217.72	218.85	.24✓	.41✓	4.11	.12
218.85	219.94	5.18	9.48	59.65	1.74
219.94	220.22	N/A	N/A	N/A	-
220.22	221.38	8.58✓	24.07✓	111.07	3.24
221.38	222.11	N/A	N/A	N/A	-
222.11	222.53	1.13✓	1.82✓	18.17	.53
222.53	222.93	N/A	N/A	N/A	-
222.93	223.85	5.74✓	14.43✓	105.93	3.09
223.85	228.75	N/A	N/A	N/A	-
228.75	229.06	3.98✓	8.29✓	51.42	1.50
229.06	231.28	N/A	N/A	N/A	-
231.28	232.23	9.25✓	19.60✓	145.35	4.24
232.23	234.30	3.08✓	3.84✓	49.36	1.44
234.30	235.31	.40✓	.70✓	8.91	.26
235.31	236.01	4.20✓	6.60✓	64.45	1.88
236.01	237.74	N/A	N/A	N/A	-
237.74	239.36	3.38✓	4.26✓	50.39	1.47
239.36	240.52	.27✓	1.14✓	2.06	.06
240.52	241.71	N/A	N/A	N/A	-
241.71	243.47	1.20✓	1.74✓	15.08	.44
243.47	304.65	N/A	N/A	N/A	-
304.65	306.32	5.03✓	8.55✓	84.67	2.47
306.32	309.37	4.80✓	5.46✓	72.67	2.12
309.37	312.42	4.43✓	4.62✓	65.47	1.91
312.42	314.25	5.95✓	9.13✓	83.64	2.44
314.25	315.32	5.48✓	9.51✓	82.61	2.41
315.32	315.99	3.08✓	4.62✓	41.48	1.21
315.99	316.84	.37✓	.42✓	8.23	.24
316.84	318.30	5.48✓	6.60✓	71.65	2.09
318.30	320.34	1.28✓	1.44✓	26.05	.76
320.34	322.11	.83✓	.60✓	20.23	.59
322.11	323.70	1.42✓	1.16✓	22.28	.65
323.70	325.98	.18✓	.08✓	12.00	.35
325.98	326.56	1.15✓	1.58✓	16.11	.47
326.56	334.88	N/A	N/A	N/A	-
334.88	336.96	.82✓	1.56✓	14.05	.41
336.96	339.55	N/A	N/A	N/A	-
339.55	342.60	.62✓	1.11✓	12.00	.35
342.60	350.82	N/A	N/A	N/A	-
350.82	352.26	.23✓	.25✓	2.06	.06
352.26	354.88	2.82✓	2.64✓	31.19	.91
354.88	355.24	.95✓	.75✓	8.91	.26
355.24	410.26	N/A	N/A	N/A	-

SPENCER MOORE BUSINESS FORMS 4

HOLE NO: A-70 LATITUDE: 10700.88 AZIMUTH: 0.00
 HOLE LENGTH: 108.20 DEPARTURE: 7694.94 DIP: -90.00
 ELEVATION: 1296.69

DIP TESTS: DEPTH DIP AZIMUTH
 49.07 ✓ -86.00 ✓ 122.20 ✓
 103.94 ✓ -84.00 ✓ 143.15 ✓

INTERVAL		ASSAYS				AG
FROM	TO	PB %	ZN %	AG GM/TON	AG OZ/TON	
0.00	61.42	N/A	N/A	N/A	-	
61.42	61.97	4.58 ✓	8.00 ✓	60.33	1.76	
61.97	63.25	1.65 ✓	1.88 ✓	27.08	.79	
63.25	64.77	3.38 ✓	5.88 ✓	42.51	1.24	
64.77	66.60	6.59 ✓	14.70 ✓	112.78	3.29	
66.60	67.88	1.23 ✓	.37 ✓	17.14	.50	
67.88	69.83	1.18 ✓	1.18 ✓	14.05	.41	
69.83	72.33	N/A	N/A	N/A	-	
72.33	73.76	1.68 ✓	3.96	29.14	.85	
73.76	74.98	1.95 ✓	4.92 ✓	30.17	.88	
74.98	77.72	2.03 ✓	4.80 ✓	34.28	1.00	
77.72	79.25	1.38 ✓	2.76 ✓	19.20	.56	
79.25	81.69	1.88 ✓	4.38 ✓	30.17	.88	
81.69	82.75	1.38 ✓	3.12 ✓	22.28	.65	
82.75	85.10	1.08 ✓	2.94 ✓	16.11	.47	
85.10	85.95	.98 ✓	2.70 ✓	15.08	.44	
85.95	87.78	1.75 ✓	3.72 ✓	26.05	.76	
87.78	88.39	.93 ✓	3.18 ✓	15.08	.44	
88.39	108.20	N/A	N/A	N/A	-	

HOLE NO: A-71 LATITUDE: 10783.74 AZIMUTH: 0.00
 HOLE LENGTH: 177.39 DEPARTURE: 7606.99 DIP: -90.00
 ELEVATION: 1307.62

DIP TESTS: DEPTH DIP AZIMUTH
 85.95 ✓ -77.00 ✓ 101.30 ✓
 168.25 ✓ -81.00 ✓ 101.30 ✓ *propari*

INTERVAL		ASSAYS				
FROM	TO	PB %	ZN %	AG GM/TON	AG GM/TON	
0.00	119.79	N/A	N/A	N/A		
119.79	121.77	8.77 ✓	18.41 ✓	130.95	3.82	
121.77	122.53	2.33 ✓	4.38 ✓	35.31	1.03	
122.53	124.36	3.42 ✓	7.34 ✓	49.36	1.44	
124.36	126.64	1.55 ✓	2.22 ✓	22.28	.65	
126.64	127.92	1.43 ✓	2.76 ✓	16.80	.59	20.23
127.92	129.48	1.10 ✓	1.96 ✓	16.11	.47	
129.48	131.31	1.48 ✓	2.40 ✓	22.28	.65	
131.31	134.33	3.08 ✓	4.86 ✓	35.31	1.03	
134.33	136.70	.95 ✓	2.00 ✓	15.08	.44	
136.70	137.92	.47 ✓	.70 ✓	9.94	.29	
137.92	139.66	1.40 ✓	3.18 ✓	29.14	.85	
139.66	140.39	N/A	N/A	N/A	-	
140.39	141.06	1.75 ✓	1.98 ✓	30.17	.88	
141.06	142.74	N/A	N/A	N/A	-	
142.74	144.29	.30 ✓	.96 ✓	5.14	.15	K
144.29	146.27	N/A	N/A	N/A	-	
146.27	147.46	.89 ✓	1.32 ✓	19.20	.56	
147.46	159.04	N/A	N/A	N/A	-	
159.04	161.15	2.33 ✓	2.00 ✓	32.22	.94	
161.15	163.43	1.85 ✓	1.04 ✓	24.34	.71	
163.43	165.96	1.88 ✓	1.02 ✓	21.25	.62	
165.96	168.80	3.45 ✓	2.46 ✓	36.34	1.06	
168.80	170.60	1.35 ✓	1.02 ✓	15.08	.44	
170.60	172.67	3.45 ✓	1.74 ✓	35.31	1.03	
172.67	175.26	.85 ✓	1.09 ✓	14.05	.41	
175.26	177.39	N/A	N/A	N/A	-	

SPECIFIC MODEL BUSINESS FORM 4

HOLE NO: A-72 LATITUDE: 10869.20 AZIMUTH: 0.00
 HOLE LENGTH: 195.07 DEPARTURE: 7524.17 DIP: -90.00
 ELEVATION: 1314.96

DIP TESTS: DEPTH DIP AZIMUTH
 92.05 ✓ -82.00 ✓ 96.30 ✓
 177.39 ✓ -80.00 ✓ 105.30 ✓ *fvopari*

INTERVAL		ASSAYS				AG
FROM	TO	PB %	ZN %	AG GM/TON	AG 02/TON	
0.00	154.29	N/A	N/A	N/A	-	
154.29	156.36	9.53 ✓	18.11 ✓	126.15	3.68	
156.36	157.37	5.64 ✓	12.45 ✓	79.53	2.32	
157.37	159.68	1.83 ✓	3.12 ✓	28.11	.82	
159.68	160.42	.79 ✓	.95 ✓	10.97	.32	
160.42	162.00	2.15 ✓	4.20 ✓	30.17	.88	
162.00	162.52	N/A	N/A	N/A	-	
162.52	162.85	2.50 ✓	.16 ✓	30.17	.88	
162.85	163.49	N/A	N/A	N/A	-	
163.49	165.26	.75 ✓	.76 ✓	8.91	.26	
165.26	168.25	1.04 ✓	1.46 ✓	15.08	.44	
168.25	169.77	N/A	N/A	N/A	-	
169.77	172.52	1.18 ✓	1.96 ✓	15.08	.44	
172.52	174.71	1.80 ✓	3.00 ✓	25.37	.74	
174.71	176.48	N/A	N/A	N/A	-	
176.48	177.67	1.63 ✓	2.88 ✓	20.23	.59	
177.67	180.29	.47 ✓	.77 ✓	7.20	.21	
180.29	181.05	.63 ✓	1.44 ✓	7.20	.21	
181.05	183.09	2.00 ✓	3.06 ✓	35.31	1.03	
183.09	184.31	N/A	N/A	N/A	-	
184.31	185.62	1.35 ✓	2.40 ✓	21.25	.62	
185.62	186.54	4.73 ✓	4.98 ✓	82.61	2.41	
186.54	195.07	N/A	N/A	N/A	-	

HOLE NO: A-73 LATITUDE: 10941.06 AZIMUTH: 0.00
 HOLE LENGTH: 364.24 DEPARTURE: 7676.01 DIP: -90.00
 ELEVATION: 1312.84

DIP TESTS:	DEPTH	DIP	AZIMUTH
	64.62 ✓	-89.00 ✓	101.00 ✓
	122.53 ✓	-90.00 ✓	90.30 ✓
	183.49 ✓	-73.00 ✓	94.30 ✓
	244.45 ✓	-71.00 ✓	105.30 ✓
	305.41 ✓	-69.00 ✓	99.00 ✓

trapped

INTERVAL		ASSAYS			AG
FROM	TO	PB %	ZN %	AG GM/TON	AG 02/TON
0.00	35.66	N/A	N/A	N/A	-
35.66	36.67	.54 ✓	1.04 ✓	8.91	.26
36.67	38.40	1.43 ✓	2.73 ✓	24.34	.71
38.40	39.32	1.60 ✓	3.42 ✓	32.22	.94
39.32	41.15	1.83 ✓	4.32 ✓	35.31	1.03
41.15	42.67	1.38 ✓	1.30 ✓	27.42	.80
42.67	46.02	N/A	N/A	N/A	-
46.02	46.94	3.60 ✓	9.54 ✓	66.50	1.94
46.94	61.08	N/A	N/A	N/A	-
61.08	63.79	2.48 ✓	4.56 ✓	37.37	1.09
63.79	64.62	N/A	N/A	N/A	-
64.62	66.26	1.95 ✓	3.84 ✓	30.17	.88
66.26	68.43	3.08 ✓	5.04 ✓	45.25	1.32
68.43	69.83	2.38 ✓	3.72 ✓	38.39	1.12
69.83	72.18	2.29 ✓	4.86 ✓	38.39	1.12
72.18	73.70	2.50 ✓	6.01 ✓	40.45	1.18
73.70	75.29	1.00 ✓	1.92 ✓	18.17	.53
75.29	77.11	.35 ✓	.42 ✓	3.09	.09
77.11	79.86	8.86 ✓	14.93 ✓	128.21	3.74
79.86	81.38	4.20 ✓	5.28 ✓	58.62	1.71
81.38	84.43	3.45 ✓	7.32 ✓	50.39	1.47
84.43	86.38	4.13 ✓	7.30 ✓	55.53	1.62
86.38	88.15	1.95 ✓	5.76 ✓	25.37	.74
88.15	90.53	2.15 ✓	4.86 ✓	32.22	.94
90.53	92.35	2.08 ✓	3.48 ✓	28.11	.82
92.35	94.18	5.93 ✓	12.58 ✓	90.84	2.65
94.18	95.25	2.78 ✓	5.16 ✓	44.22	1.29
95.25	97.38	2.93 ✓	7.68 ✓	46.28	1.35
97.38	98.60	N/A	N/A	N/A	-
98.60	99.52	1.00 ✓	4.26 ✓	18.17	.53
99.52	100.07	N/A	N/A	N/A	-
100.07	100.64	2.40 ✓	7.02 ✓	39.42	1.15
100.64	103.39 103.54	5.84 ✓	10.45 ✓	88.79	2.59
103.39	299.01	N/A	N/A	N/A	-
299.01	300.81	3.83 ✓	7.68 ✓	51.42	1.56
300.81	301.29	N/A	N/A	N/A	-
301.29	304.28	5.84 ✓	7.64 ✓	78.50	2.29
304.28	304.50	.18 ✓	.28 ✓	5.14	.15
304.50	364.24	N/A	N/A	N/A	-

SHEET-LO MOORE BUSINESS FORMS 4

HOLE NO: A-74 LATITUDE: 10525.90 AZIMUTH: 0.00
HOLE LENGTH: 323.09 DEPARTURE: 7612.95 DIP: -90.00
ELEVATION: 1283.48

DIP TESTS: DEPTH DIP AZIMUTH
61.57 ✓ -85.00 ✓ 110.30 ✓
122.53 ✓ -82.00 ✓ 80.00 ✓ 71.9 tropari
183.49 ✓ -78.00 ✓ 59.30 ✓
244.45 ✓ -73.00 ✓ 58.30 ✓

INTERVAL		ASSAYS					AG
FROM	TO	PB	ZN	AG		02/TON	
		%	%	GM/TON			
0.00	93.88	N/A	N/A	N/A		-	
93.88	96.47	2.58 .60 ✓	.33 ✓	8.23		.24	
96.47	98.45	1.98 1.53 ✓	1.40 ✓	20.23	①	.59	
98.45	99.67	1.22 4.43 ✓	1.22 ✓	47.31		1.38	
99.67	102.41	2.79 .14 ✓	.26 ✓	8.23		.24	
102.41	104.39	1.98 .45 ✓	.25 ✓	12.00		.35	
104.39	107.44	3.05 .15 ✓	.14 ✓	6.17	②	.18	
107.44	109.73	2.29 .12 ✓	.21 ✓	7.20		.21	
109.73	112.17	2.49 .15 ✓	.40 ✓	8.23		.24	
112.17	112.78	N/A .18	N/A .40	N/A?	5.14	.15 sample 1468	
112.78	114.30	1.52 .13 ✓	.36 ✓	6.17		.18	
114.30	157.03	N/A	N/A	N/A		-	
157.03	158.95	1.92 1.03 ✓	.70 ✓	14.05		.41	
158.95	160.32	N/A	N/A	N/A		-	
160.32	162.92	2.60 3.23 ✓	3.18 ✓	34.28	③	1.00	
162.92	165.51	2.59 .15 ✓	.13 ✓	9.94		.29	
165.51	167.94	2.43 .12 ✓	.11 ✓	8.23	④	.24	
167.94	171.30	3.36 .17 ✓	.24 ✓	9.94		.29	
171.30	172.82	1.52 .10 ✓	.14 ✓	2.06		.06	
172.82	174.04	1.22 2.18 ✓	3.00 ✓	25.37	①	.74	
174.04	175.26	1.22 4.50 ✓	5.55 ✓	54.51		1.59	
175.26	176.69	1.43 .20 ✓	.28 ✓	8.91		.26	
176.69	178.25	N/A	N/A	N/A		-	
178.25	181.30	3.05 .18 ✓	.42 ✓	8.91		.26	
181.30	181.45	.15 N/A	N/A	N/A		-	
181.45	184.56	3.11 .24 ✓	.51 ✓	13.03	②	.38	
184.56	185.01	.45 N/A	N/A	N/A		-	
185.01	186.93	1.92 1.95 ✓	3.24 ✓	30.17		.88	
186.93	187.91	N/A	N/A	N/A		-	
187.91	191.11	3.20 .10 ✓	.24 ✓	7.20		.21	
191.11	194.31	3.20 .20 ✓	.15 ✓	8.23		.24	
194.31	197.51	3.20 .60 ✓	.13 ✓	14.05		.41	
197.51	200.56	3.05 .07 ✓	.19 ✓	6.17		.18	
200.56	202.69	2.13 .12 ✓	.21 ✓	8.23		.24	
202.69	205.13	2.44 .43 ✓	.20 ✓	10.97	⑤	.32	
205.13	206.81	1.68 3.08 ✓	2.94 ✓	37.37		1.69	
206.81	208.18	1.37 .24 ✓	.16 ✓	8.91		.26	
208.18	209.64	1.46 .43 ✓	.32 ✓	10.97		.32	
209.64	210.62	.98 .25 ✓	.22 ✓	9.94		.29	
210.62	211.93	1.31 6.53 ✓	7.54 ✓	82.61		2.41	
211.93	214.58	3.65 .80 ✓	.83 ✓	9.94		.29	
214.58	223.21	N/A	N/A	N/A		-	
223.21	224.85	1.64 1.63 ✓	1.20 ✓	20.23		.59	
224.85	296.88	N/A	N/A	N/A		-	

HOLE NO: A-74

INTERVAL		ASSAYS				
FROM	TO	PB %	ZN %	AG GM/TON	AG OZ/TON	
296.88	298.70	1.82	.03 ✓	.11 ✓	2.06	.06
298.70	323.09	N/A	N/A	N/A	—	

SPECFIC MOORE BUSINESS FORMS 4

HOLE NO: A-75 LATITUDE: 11000.76 AZIMUTH: 0.00
HOLE LENGTH: 347.78 DEPARTURE: 7641.05 DIP: -90.00
ELEVATION: 1311.83

DIP TESTS:	DEPTH	DIP	AZIMUTH
	61.57 ✓	-88.00 ✓	280.00 ✓
	134.72 ✓	-87.00 ✓	69.30 ✓
	201.78 ✓	-85.00 ✓	13.00 ✓
	262.74 ✓	-83.00 ✓	37.00 ✓
	323.70 ✓	-80.00 ✓	81.00 ✓

Tropari

INTERVAL		ASSAYS				
FROM	TO	PB %	ZN %	AG GM/TON	AG OZ/TON	
0.00	26.21	N/A	N/A	N/A	-	
26.21	27.74	2.28 ✓	5.58 ✓	40.45	1.18	
27.74	28.96	1.60 ✓	3.84 ✓	26.05	.76	
28.96	30.48	2.00 ✓	4.02 ✓	31.19	.91	
30.48	32.61	1.85 ✓	3.90 ✓	30.17	.88	
32.61	35.05	N/A 1.23	N/A 3.30	N/A 15.08	.44	Sample 1795
35.05	35.97	2.20 ✓	3.48 ✓	34.28	1.00	
35.97	37.49	2.35 ✓	4.32 ✓	31.19	.91	
37.49	39.01	1.65 ✓	3.06 ✓	24.34	.71	
39.01	40.84	N/A 1.23	N/A 4.59	N/A 18.17	.53	Sample 1796
40.84	42.06	2.18 ✓	5.88 ✓	31.19	.91	
42.06	43.59	1.48 ✓	3.48 ✓	24.34	.71	
43.59	44.81	1.63 ✓	3.78 ✓	24.34	.71	
44.81	45.87	2.20 ✓	5.76 ✓	39.42	1.15	
45.87	47.24	.34 ✓	1.90 ✓	6.17	.18	
47.24	48.77	3.30 ✓	5.22 ✓	50.39	1.47	
48.77	50.44	.28 ✓	.96 ✓	5.14	.15	
50.44	51.48	2.93 ✓	5.88 ✓	45.25	1.32	
51.48	53.64	N/A	N/A	N/A	-	
53.64	56.69	1.60 ✓	1.96 ✓	21.25	.62	
56.69	58.83	1.48 ✓	3.36 ✓	22.28	.65	
58.83	59.59	1.93 ✓	4.50 ✓	34.28	1.00	
59.59	61.26	3.90 ✓	9.08 ✓	64.45	1.88	
61.26	62.79	3.15 ✓	5.16 ✓	43.19	1.26	
62.79	64.92	4.35 ✓	6.36 ✓	57.59	1.68	
64.92	67.67	1.95 ✓	3.30 ✓	30.17	.88	
67.67	68.37	N/A	N/A	N/A	-	
68.37	69.80	2.85 ✓	4.50 ✓	37.37	1.09	
69.80	71.63	2.13 ✓	3.96 ✓	35.31	1.03	
71.63	72.85	1.40 ✓	3.54 ✓	20.23	.59	
72.85	73.91	2.43 ✓	5.40 ✓	35.31	1.03	
73.91	75.13	N/A	N/A	N/A	-	
75.13	75.90	1.45 ✓	4.74 ✓	20.23	.59	
75.90	77.42	3.60 ✓	10.82 ✓	50.39	1.47	
77.42	78.94	3.60 ✓	7.08 ✓	60.33	1.76	
78.94	80.47	3.45 ✓	5.64 ✓	51.42	1.50	
80.47	82.08	4.05 ✓	7.08 ✓	56.56	1.65	
82.08	84.06	.70 ✓	2.58 ✓	9.94	.29	
84.06	85.77	4.43 ✓	7.68 ✓	60.33	1.76	
85.77	87.78	2.33 ✓	4.44 ✓	34.28	1.00	
87.78	89.12	3.53 ✓	6.48 ✓	47.31	1.38	
89.12	90.83	4.99 ✓	8.76 ✓	70.62	2.06	
90.83	91.87	3.68 ✓	7.80 ✓	48.33	1.41	

J

HOLE NO: A-75

INTERVAL		ASSAYS				
FROM	TO	PB %	ZN %	AG GM/TON	AG OZ/TON	
91.87	92.29	N/A	N/A	N/A	-	
92.29	93.88	1.63 ✓	3.60 ✓	24.34	.71	
93.88	96.32	1.10 ✓	3.10 ✓	15.08	.44	3.12
96.32	97.84	2.25 ✓	7.08 ✓	34.28	1.00	
97.84	99.06	3.23 ✓	6.72 ✓	40.45	1.18	
99.06	100.28	3.98 ✓	6.60 ✓	52.45	1.53	
100.28	103.33	6.09 ✓	14.43 ✓	80.56	2.35	
103.33	104.70	3.23 ✓	8.97 ✓	53.48	1.56	
104.70	106.22	2.38 ✓	5.34 ✓	35.31	1.03	
106.22	107.75	4.95 ✓	6.36 ✓	59.30	1.73	
107.75	108.66	2.85 ✓	5.64 ✓	45.25	1.32	
108.66	109.09	N/A	N/A	N/A	-	
109.09	110.95	3.08 ✓	5.88 ✓	40.45	1.18	
110.95	245.03	N/A	N/A	N/A	-	
245.03	246.55	12.75 ✓	9.23 ✓	171.40	5.00	
246.55	249.05	N/A	N/A	N/A	-	
249.05	250.58	6.68 ✓	5.16 ✓	78.50	2.29	
250.58	252.25	6.08 ✓	4.20 ✓	67.53	1.97	
252.25	253.04	N/A	N/A	N/A	-	
253.04	253.59	4.13 ✓	10.89 ✓	59.65	1.74	
253.59	254.66	3.90 ✓	7.44 ✓	57.59	1.68	
254.66	259.38	N/A	N/A	N/A	-	
259.38	261.40	5.40 ✓	10.50 ✓	81.59	2.38	
261.40	262.52	4.50 ✓	8.23 ✓	67.53	1.97	
262.52	262.83	N/A	N/A	N/A	-	
262.83	264.26	4.80 ✓	7.62 ✓	70.62	2.06	
264.26	264.93	5.10 ✓	8.56 ✓	74.73	2.18	
264.93	347.78	N/A	N/A	N/A	-	

HOLE NO: A-76
HOLE LENGTH: 407.21

LATITUDE: 10998.77
DEPARTURE: 7559.52
ELEVATION: 1312.38

AZIMUTH: 0.00
DIP: -90.00

DIP TESTS:	DEPTH	DIP	AZIMUTH
	61.57 ✓	-89.00 ✓	130.00 ✓
	122.53 ✓	-84.00 ✓	138.00 ✓
	183.49 ✓	-80.00 ✓	146.00 ✓
	244.45 ✓	-89.00 ✓	142.00 ✓
	305.41 ✓	-83.00 ✓	154.00 ✓
	387.70 ✓	-83.00 ✓	136.00 ✓

tropari

INTERVAL		ASSAYS			AG
FROM	TO	PB %	ZN %	AG GM/TON	AG OZ/TON
0.00	113.08	N/A	N/A	N/A	-
113.08	114.00	2.10 ✓	4.44 ✓	20.23	.59
114.00	115.37	N/A	N/A	N/A	-
115.37	115.98	1.50 ✓	2.46 ✓	23.31	.68
115.98	139.54	N/A	N/A	N/A	-
139.54	140.51	6.70 ✓	10.65 ✓	62.39	1.82
140.51	142.10	4.65 ✓	7.20 ✓	66.50	1.94
142.10	143.56	3.75 ✓	5.28 ✓	52.45	1.53
143.56	144.11	N/A	N/A	N/A	-
144.11	145.88	2.23 ✓	3.84 ✓	30.17	.88
145.88	147.10	2.63 ✓	3.48 ✓	28.11	.82
147.10	149.32	1.90 ✓	1.68	24.34	.71
149.32	251.22	N/A	N/A	N/A	-
251.22	252.83	9.34 ✓	13.23 ✓	141.23	4.12
252.83	274.41	N/A	N/A	N/A	-
274.41	276.24	2.45 ✓	5.52 ✓	45.25	1.32
276.24	280.81	N/A	N/A	N/A	-
280.81	282.34	2.30 ✓	3.18 ✓	35.31	1.03
282.34	284.50	N/A	N/A	N/A	-
284.50	285.38	6.94 ✓	7.68 ✓	91.87	2.68
285.38	285.81	N/A	N/A	N/A	-
285.81	287.43	5.18	4.92 ✓	63.42	1.85
287.43	292.82	N/A	N/A	N/A	-
292.82	293.58	9.45 ✓	14.36 ✓	115.87	3.38
293.58	336.93	N/A	N/A	N/A	-
336.93	337.84	.10 ✓	.10 ✓	1.03	.03
337.84	338.36	6.44 ✓	11.65 ✓	68.56	2.00
338.36	339.27	.02 ✓	.06 ✓	1.03	.03
339.27	341.68	N/A	N/A	N/A	-
341.68	343.97	2.35 ✓	3.48 ✓	35.31	1.03
343.97	364.85	N/A	N/A	N/A	-
364.85	366.46	4.35 ✓	4.44 ✓	52.45	1.53
366.46	367.80	N/A	N/A	N/A	-
367.80	369.42	3.15 ✓	3.06 ✓	40.45	1.18
369.42	370.64	1.00 ✓	.31 ✓	12.00	.35
370.64	372.16	4.73 ✓	3.60 ✓	48.33	1.41
372.16	373.38	1.60 ✓	.22 ✓	9.94	.29
373.38	374.45	5.37 ✓	4.20 ✓	48.33	1.41
374.45	375.67	.59 ✓	.27 ✓	10.97	.32
375.67	377.34	5.03 ✓	3.66 ✓	50.39	1.47
377.34	378.71	4.05	3.42 ✓	39.42	1.15
378.71	407.21	N/A	N/A	N/A	-

SPRINTING MOORE BUSINESS FORMS 4

HOLE NO: A-76

INTERVAL		ASSAYS		
FROM	TO	PB %	ZN %	AG GM/TON

HOLE NO: A-77 LATITUDE: 10444.88 AZIMUTH: 0.00
 HOLE LENGTH: 305.41 DEPARTURE: 7699.64 DIP: -90.00
 ELEVATION: 1278.23

DIP TESTS:	DEPTH	DIP	AZIMUTH
	52.42 ✓	-87.00 ✓	69.00 ✓
	104.24 ✓	-83.00 ✓	79.00 ✓
	165.20 ✓	-79.00 ✓	72.00 ✓
	226.16 ✓	-79.00 ✓	71.00 ✓
	305.41 ✓	-77.00 ✓	72.00 ✓

tropaxi

287.1

INTERVAL		ASSAYS			
FROM	TO	PB %	ZN %	AG GM/TON	AG OZ/TON
0.00	115.06	N/A	N/A	N/A	-
115.06	116.89	.85 ✓	.78 ✓	14.05	.41
116.89	118.32	3.45 ✓	2.82 ✓	34.28	1.00
118.32	119.02	1.28 ✓	.64 ✓	24.34	.71
119.02	121.37	3.60 ✓	2.88 ✓	40.45	1.18
121.37	123.81	.73 ✓	.52 ✓	15.08	.44
123.81	174.47	N/A	N/A	N/A	-
174.47	175.87	1.23 ✓	1.30 ✓	20.23	.59
175.87	178.06	.05 ✓	.04 ✓	4.11	.12
178.06	178.55	1.03 ✓	.98 ✓	24.34	.71
178.55	181.23	2.00 ✓	1.66 ✓	33.25	.97
181.23	182.00	.73 ✓	.40 ✓	20.23	.59
182.00	185.68	N/A	N/A	N/A	-
185.68	187.45	.63 ✓	.21 ✓	14.05	.41
187.45	189.59	2.18 ✓	2.70 ✓	27.42	.80
189.59	191.26	2.08 ✓	2.52 ✓	25.37	.74
191.26	192.63	1.28 ✓	1.16 ✓	15.08	.44
192.63	195.07	3.00 ✓	2.64 ✓	30.17	.88
195.07	196.60	1.68 ✓	1.30 ✓	19.20	.56
196.60	198.39	1.38 ✓	1.18 ✓	16.11	.47
198.39	199.80	2.70 ✓	2.46 ✓	31.19	.91
199.80	202.08	2.38 ✓	2.28 ✓	30.17	.88
202.08	204.83	1.73 ✓	1.36 ✓	20.23	.59
204.83	237.29	N/A	N/A	N/A	-
237.29	238.23	.37 ✓	.63 ✓	6.17	.18
238.23	239.69	3.15 ✓	2.28 ✓	41.48	1.21
239.69	241.34	.95 ✓	.72 ✓	10.97	.32
241.34	243.87	3.08 ✓	2.82 ✓	41.48	1.21
243.87	246.19	2.70 ✓	.74 ✓	40.45	1.18
246.19	248.11	.15 ✓	.14 ✓	2.06	.06
248.11	258.32	N/A	N/A	N/A	-
258.32	259.69	.08 ✓	.03 ✓	1.03	.03
259.69	305.41	N/A	N/A	N/A	-

SHEET 10 MOORE BUSINESS FORMS 4

HOLE NO: A-78 LATITUDE: 11046.27 AZIMUTH: 0.00
 HOLE LENGTH: 310.90 DEPARTURE: 7689.80 DIP: -90.00
 ELEVATION: 1311.67

DIP TESTS: DEPTH DIP AZIMUTH
 61.57 ✓ -89.00 ✓ 106.00 ✓
 122.53 ✓ -80.30 ✓ 122.00 ✓
 183.49 ✓ ~~-85.42~~ 118.00 ✓
 244.45 ✓ -70.00 ✓ 121.00 ✓ 1/4.8
 299.31 ✓ -69.30 ✓ 27.00 ✓

tropari

INTERVAL		ASSAYS			AG	
FROM	TO	PB %	ZN %	AG GM/TON	AG 02/TON	
0.00	51.66	N/A	N/A	N/A	-	
51.66	53.19	5.40 ✓	9.20	90.84	2.65	9.22
53.19	54.62	N/A	N/A	N/A	-	
54.62	55.32	6.38 ✓	13.30 ✓	90.84	2.65	
55.32	56.85	N/A	N/A	N/A	-	
56.85	58.00	3.90 ✓	8.04 ✓	59.65	1.74	
58.00	74.58	N/A	N/A	N/A	-	
74.58	76.08	5.03 ✓	4.80	65.47	1.91	
76.08	78.64	N/A	N/A	N/A	-	
78.64	80.77	8.72 ✓	14.83 ✓	126.15	3.68	
80.77	82.60	2.45 ✓	4.14 ✓	37.37	1.09	
82.60	83.97	3.90 ✓	6.84 ✓	54.51	1.59	
83.97	85.34	1.68 ✓	4.20 ✓	28.11	.82	
85.34	85.95	1.83 ✓	3.00 ✓	27.08	.79	
85.95	262.71	N/A	N/A	N/A	-	
262.71	263.90	5.10 ✓	5.40 ✓	64.45	1.88	
263.90	264.08	N/A	N/A	N/A	-	
264.08	264.87	1.83 ✓	3.18 ✓	25.37	.74	
264.87	265.18	N/A	N/A	N/A	-	
265.18	266.70	1.23 ✓	3.00 ✓	20.23	.59	
266.70	267.61	3.75 ✓	6.36 ✓	75.76	2.21	
267.61	284.13	N/A	N/A	N/A	-	
284.13	286.05	5.25 ✓	7.20 ✓	89.81	2.62	
286.05	287.43	1.50 ✓	3.00 ✓	20.23	.59	
287.43	288.95	1.88 ✓	3.24 ✓	24.34	.71	
288.95	290.17	1.90 ✓	3.72 ✓	26.05	.76	
290.17	291.39	1.15 ✓	1.18 ✓	20.23	.59	
291.39	293.52	1.80 ✓	4.38 ✓	31.19	.91	
293.52	294.13	.59 ✓	.94 ✓	8.23	.24	
294.13	310.90	N/A	N/A	N/A	-	

SPEECH-O-MATH BUSINESS FORMS 4

HOLE NO: A-79
 HOLE LENGTH: 419.10

LATITUDE: 11045.78
 DEPARTURE: 7597.11
 ELEVATION: 1312.16

AZIMUTH: 0.00
 DIP: -90.00

DIP TESTS:	DEPTH	DIP	AZIMUTH
	60.96 ✓	-89.00 ✓	165.56 ✓
	121.92 ✓	-87.00 ✓	139.40 ✓
	182.88 ✓	-85.00 ✓	136.56 ✓
	243.84 ✓	-86.00 ✓	145.50 ✓
	316.99 ✓	-82.00 ✓	319.50 ✓
	377.95 ✓	-81.00 ✓	105.44 ✓

INTERVAL		ASSAYS				AG	
FROM	TO	PB %	ZN %	AG GM/TON	AG 02/TON		
0.00	61.72	N/A	N/A	N/A	-		
61.72	63.09	1.77	4.44 ✓	28.11	.82	1.70	
63.09	65.38	2.30 ✓	4.14 ✓	32.22	.94		
65.38	74.68	N/A	N/A	N/A	-		
74.68	76.17	2.78 ✓	3.78 ✓	38.39	1.12		
76.17	77.36	N/A	N/A	N/A	-		
77.36	78.64	.48 ✓	1.08 ✓	7.20	.21		
78.64	80.01	1.83 ✓	4.08 ✓	28.11	.82		
80.01	80.92	N/A	N/A	N/A	-		
80.92	82.20	1.68 ✓	4.08 ✓	22.28	.65		
82.20	84.00	1.78 ✓	3.66 ✓	27.08	.79		
84.00	84.80	N/A	N/A	N/A	-		
84.80	86.29	1.83 ✓	3.72 ✓	30.17	.88		
86.29	89.31	N/A	N/A	N/A	-		
89.31	90.83	3.30 ✓	5.46 ✓	45.25	1.32		
90.83	92.51	2.93 ✓	5.40 ✓	37.37	1.09		
92.51	96.01	4.13 ✓	2.82 ✓	44.22	1.29		
96.01	97.38	1.58 ✓	1.94 ✓	25.37	.74		
97.38	99.36	1.35 ✓	2.46 ✓	23.31	.68		
99.36	100.89	2.50 ✓	4.26 ✓	35.31	1.03		
100.89	102.41	1.48 ✓	3.00 ✓	21.25	.62		
102.41	104.24	1.90 ✓	4.14 ✓	29.14	.85		
104.24	106.83	N/A	N/A	N/A	-		
106.83	109.73	.93 ✓	1.84 ✓	15.08	.44		
109.73	114.15	N/A	N/A	N/A	-		
114.15	115.67	1.19 ✓	3.60 ✓	20.23	.59		
115.67	116.89	4.50 ✓	5.28 ✓	60.33	1.76		
116.89	118.14	N/A	N/A	N/A	-		
118.14	119.48	2.78 ✓	6.48 ✓	49.36	1.44		
119.48	121.68	6.17 ✓	10.92 ✓	100.78	2.94		
121.68	286.51	N/A	N/A	N/A	-		
286.51	287.58	.85 ✓	1.74 ✓	12.00	.35		
287.58	289.41	2.23 ✓	4.26 ✓	39.42	1.15		
289.41	289.83	N/A	N/A	N/A	-		
289.83	291.79	2.28 ✓	3.60 ✓	36.34	1.06		
291.79	292.52	2.33 ✓	2.46 ✓	28.11	.82		
292.52	344.64	N/A	N/A	N/A	-		
344.64	346.25	5.84 ✓	5.40 ✓	61.36	1.79		
346.25	347.78	8.11 ✓	8.11 ✓	87.76	2.56		
347.78	349.30	5.71 ✓	6.12 ✓	63.08	1.84		
349.30	350.52	7.21 ✓	8.22 ✓	74.73	2.18		
350.52	352.04	4.20 ✓	6.36 ✓	53.48	1.56		

SPECIAL ORDER BUSINESS FORMS 4

HOLE NO: A-80 LATITUDE: 11090.02 AZIMUTH: 0.00
 HOLE LENGTH: 346.25 DEPARTURE: 7733.92 DIP: -90.00
 ELEVATION: 1310.56

DIP TESTS:	DEPTH	DIP	AZIMUTH
	61.57 ✓	-87.15 ✓	144.00 ✓
	122.53 ✓	-86.00 ✓	128.50 ✓
	183.49 ✓	-71.40 ✓	128.10 ✓
	244.45 ✓	-68.50 ✓	119.50 ✓
	305.41 ✓	-64.40 ✓	109.50 ✓

trough

INTERVAL		ASSAYS			
FROM	TO	PB %	ZN %	AG GM/TON	AG OZ/TON
0.00	264.87	N/A	N/A	N/A	-
264.87	266.55	.70 ✓	1.44 ✓	8.23	.24
266.55	268.07	1.10 ✓	1.80 ✓	15.08	.44
268.07	269.75	1.25 ✓	2.34 ✓	18.17	.53
269.75	346.25	N/A	N/A	N/A	-

HOLE NO: A-81 LATITUDE: 10403.99 AZIMUTH: 0.00
 HOLE LENGTH: 273.71 DEPARTURE: 7739.45 DIP: -90.00
 ELEVATION: 1275.39

DIP TESTS:	DEPTH	DIP	AZIMUTH
	65.84 ✓	-85.00 ✓	22.20 ✓
	126.79 ✓	-80.05 ✓	59.50 ✓
	187.76 ✓	-79.20 ✓	75.00 ✓
	248.72 ✓	-79.10 ✓	65.00 ✓

INTERVAL		ASSAYS				AG
FROM	TO	PB	ZN	AG	AG	
		%	%	GM/TON	02/TON	
0.00	54.56	N/A	N/A	N/A	-	
54.56	56.39	.40 ✓	.37 ✓	5.14	.15	
56.39	57.91	2.23 ✓	1.91 ✓	34.28	1.00	
57.91	59.44	.19 ✓	.38 ✓	9.94	.29	
59.44	60.35	N/A	N/A	N/A	-	
60.35	63.09	.75 ✓	.68 ✓	18.17	.53	
63.09	64.62	13.92 ✓	11.72 ✓	156.32	4.56	
64.62	67.06	1.10 ✓	1.22 ✓	17.14	.50	
67.06	68.28	12.52 ✓	10.53 ✓	143.29	4.18	
68.28	69.80	6.78 ✓	8.16 ✓	77.47	2.26	
69.80	71.02	10.50 ✓	9.79 ✓	122.04	3.56	
71.02	173.28	N/A	N/A	N/A	-	
173.28	174.96	1.08 ✓	.88 ✓	16.11	.47	1.05
174.96	176.48	2.13 ✓	2.34 ✓	26.05	.76	
176.48	177.79	2.00 ✓	1.90 ✓	25.37	.74	
177.79	184.25	N/A	N/A	N/A	-	
184.25	185.78	2.63 ✓	2.64 ✓	37.37	1.09	
185.78	187.45	2.70 ✓	2.64 ✓	35.31	1.03	
187.45	187.97	N/A	N/A	N/A	-	
187.97	189.49	2.25 ✓	2.64 ✓	27.08	.79	
189.49	191.02	1.68 ✓	1.52 ✓	21.25	.62	
191.02	192.54	1.88 ✓	1.80 ✓	25.37	.74	
192.54	193.64	2.25 ✓	2.58 ✓	34.28	1.00	
193.64	273.71	N/A	N/A	N/A	-	

SPECIFIC MODEL BUSINESS FORM 4

HOLE NO: A-82
HOLE LENGTH: 364.24

LATITUDE: 10961.25
DEPARTURE: 7606.81
ELEVATION: 1312.30

AZIMUTH: 0.00
DIP: -90.00

DIP TESTS:	DEPTH	DIP	AZIMUTH
	61.57 ✓	-85.00 ✓	148.50 ✓
	122.53 ✓	-79.00 ✓	146.20 ✓
	183.49 ✓	-76.00 ✓	147.50 ✓
	238.35 ✓	-77.00 ✓	132.50 ✓
	293.22 ✓	-78.00 ✓	118.50 ✓
	364.23 ✓	-77.00 ✓	119.50 ✓

+Vopari

360.3

INTERVAL		ASSAYS				AG
FROM	TO	PB %	ZN %	AG GM/TON	AG OZ/TON	
0.00	97.54	N/A	N/A	N/A	-	
98.54	98.91 ³⁰	2.78 ✓	5.04 ✓	20.23	.59	
98.90	102.17 ²³	N/A	N/A	N/A	-	
102.23	103.94 ⁶	1.80 ✓	3.06 ✓	28.45	.83	
103.86	105.16	1.98 ✓	3.42 ✓	28.45	.83	
105.16	114.30	N/A	N/A	N/A	-	
114.30	115.82	1.63 ✓	3.60 ✓	33.25	.97	
115.82	118.72	N/A	N/A	N/A	-	
118.72	120.70	6.15 ✓	10.37 ✓	91.87	2.68	
120.70	121.77	N/A	N/A	N/A	-	
121.77	123.44	2.08 ✓	3.30 ✓	44.22	1.29	
123.44	124.91	2.05 ✓	3.12 ✓	44.22	1.29	
124.91	137.10	N/A	N/A	N/A	-	
137.10	138.93	3.30 ✓	6.45 ✓	41.48	1.21	
138.93	273.41	N/A	N/A	N/A	-	
273.41	274.14	4.72 ✓	9.40 ✓	90.84	2.65	
274.14	292.21	N/A	N/A	N/A	-	
292.21	293.74	3.53 ✓	4.44 ✓	54.51	1.59	
293.74	295.20	2.23 ✓	4.44 ✓	33.25	.97	
295.20	313.33	N/A	N/A	N/A	-	
313.33	315.47	.90 ✓	.94 ✓	9.94	.29	
315.47	320.65	N/A	N/A	N/A	-	
320.65	322.17	4.92 ✓	6.35 ✓	72.67	2.12	
322.17	327.05	N/A	N/A	N/A	-	
327.05	328.73	4.28 ✓	3.18 ✓	45.25	1.32	
328.73	330.25	3.98 ✓	1.34 ✓	40.45	1.18	
330.25	331.77	1.38 ✓	1.86 ✓	16.11	.47	
331.77	333.30	1.34 ✓	1.56 ✓	19.20	.56	
333.30	334.82	2.20 ✓	3.78 ✓	23.31	.68	
334.82	336.35	1.45 ✓	2.73 ✓	18.17	.53	
336.35	337.87	.49 ✓	.89 ✓	7.20	.21	
337.87	339.39	.54 ✓	.88 ✓	8.91	.26	
339.39	340.92	.48 ✓	.54 ✓	9.94	.29	
340.92	342.44	.38 ✓	.35 ✓	8.91	.26	
342.44	343.97	.27 ✓	.47 ✓	7.20	.21	
343.97	345.49	.35 ✓	.29 ✓	9.94	.29	
345.49	364.24	N/A	N/A	N/A	-	

SHEET/LO MOORE BUSINESS FORMS 4

HOLE NO: A-83 LATITUDE: 10608.52 AZIMUTH: 0.00
 HOLE LENGTH: 360.88 DEPARTURE: 7526.49 DIP: -90.00
 ELEVATION: 1289.13

DIP TESTS:	DEPTH	DIP	AZIMUTH
	53.65 ✓	-86.36 ✓	112.20 ✓
	120.09 ✓	-80.18 ✓	112.20 ✓
	181.05 ✓	-76.24 ✓	104.20 ✓
	242.01 ✓	-78.00 ✓	83.50 ✓
	302.97 ✓	-79.00 ✓	66.20 ✓
	357.83 ✓	-78.20 ✓	18.20 ✓

INTERVAL		ASSAYS			AG
FROM	TO	PB %	ZN %	AG GM/TON	AG 02/TON
0.00	138.38	N/A	N/A	N/A	-
138.38	140.82	5.20 ✓	3.66 ✓	72.67	2.12
140.82	141.27	N/A	N/A	N/A	-
141.27	144.32	3.53 ✓	3.12 ✓	44.22	1.29
144.32	145.08	1.65 ✓	1.98 ✓	20.23	.59
145.08	192.48	N/A	N/A	N/A	-
192.48	192.79	1.65 ✓	3.18 ✓	28.45	.83
192.79	192.91	3.08 ✓	4.14 ✓	55.53	1.62
192.91	193.52	2.30 ✓	3.06 ✓	30.17	.88
193.52	194.01	1.95 ✓	2.58 ✓	27.42	.80
194.01	195.53	.43 ✓	.44 ✓	9.94	.29
195.53	197.39	.34 ✓	.20 ✓	7.20	.21
197.39	197.66	1.33 ✓	1.22 ✓	17.14	.50
197.66	222.20	N/A	N/A	N/A	-
222.20	223.72	1.03 ✓	.95 ✓	20.23	.59
223.72	238.35	N/A	N/A	N/A	-
238.35	241.40	.10 ✓	.46 ✓	5.14	.15
241.40	254.51	N/A	N/A	N/A	-
254.51	256.95	.10 ✓	.07 ✓	4.11	.12
256.95	258.41	N/A	N/A	N/A	-
258.41	259.08	1.08 ✓	1.26 ✓	16.11	.47
259.08	260.60	1.60 ✓	1.92 ✓	26.40	.77
260.60	262.28	1.38 ✓	1.60 ✓	20.23	.59
262.28	263.26	1.20 ✓	1.62 ✓	21.25	.62
263.26	273.10	N/A	N/A	N/A	-
273.10	274.02	1.18 ✓	1.08 ✓	16.11	.47
274.02	360.88	N/A	N/A	N/A	-

SPECIALIZED BUSINESS FORMS

HOLE NO: A-84 LATITUDE: 10782.49 AZIMUTH: 0.00
HOLE LENGTH: 456.59 DEPARTURE: 7435.08 DIP: -90.00
ELEVATION: 1307.89

DIP TESTS: DEPTH DIP AZIMUTH

85.34 ✓	-85.00 ✓	93.50 ✓
146.30 ✓	-82.00 ✓	119.50 ✓
207.26 ✓	-85.00 ✓	111.50 ✓
268.22 ✓	-85.00 ✓	79.50 ✓
329.18 ✓	-85.00 ✓	75.20 ✓
396.2 (426.72)	-89.00 ✓	38.20 ✓

Tropari

INTERVAL		ASSAYS			
FROM	TO	PB %	ZN %	AG GM/TON	AG O2/TON
0.00	148.74	N/A	N/A	N/A	-
148.74	149.35	1.39 ✓	.67 ✓	17.14	.50
149.35	150.88	N/A	N/A	N/A	-
150.88	153.31	1.58 ✓	1.50 ✓	20.23	.59
153.31	215.49	N/A	N/A	N/A	-
215.49	216.71	3.08 ✓	4.86 ✓	45.25	1.32
216.71	219.15	5.63 ✓	8.88 ✓	91.87	2.68
219.15	253.29	N/A	N/A	N/A	-
253.29	254.60	1.30 ✓	1.84 ✓	20.23	.59
254.60	255.85	4.93 ✓	5.10 ✓	54.51	1.59
255.85	257.89	.47 ✓	.62 ✓	10.97	.32
257.89	259.08	1.38 ✓	1.08 ✓	24.34	.71
259.08	277.37	N/A	N/A	N/A	-
277.37	278.89	1.18 ✓	1.02 ✓	20.23	.59
278.89	281.18	.95 ✓	.70 ✓	19.20	.56
281.18	282.70	N/A	N/A	N/A	-
282.70	284.23	.05 ✓	.40 ✓	1.03	.03
284.23	285.75	.43 ✓	.30 ✓	13.03	.38
285.75	286.82	.12 ✓	.07 ✓	7.20	.21
286.82	318.52	N/A	N/A	N/A	-
318.52	319.28	3.53 ✓	2.46 ✓	40.45	1.18
319.28	456.59	N/A	N/A	N/A	-

SPECIALTY LOAN BUSINESS FORMS 4

HOLE NO: A-85 LATITUDE: 10953.21 AZIMUTH: 0.00
 HOLE LENGTH: 430.99 DEPARTURE: 7431.50 DIP: -90.00
 ELEVATION: 1318.21

DIP TESTS:	DEPTH	DIP	AZIMUTH
	60.96 ✓	-87.30 ✓	78.50 ✓
	121.92 ✓	-84.00 ✓	105.20 ✓
	182.88 ✓	-83.00 ✓	104.50 ✓
	243.84 ✓	-83.12 ✓	137.20 ✓
	304.80 ✓	-82.18 ✓	180.20 ✓
	384.05 ✓	-82.30 ✓	183.20 ✓
	402.34 ✓	-82.24 ✓	183.20 ✓

INTERVAL		ASSAYS			AG
FROM	TO	PB	ZN	AG	AG
		%	%	GM/TON	02/TON
0.00	181.36	N/A	N/A	N/A	-
181.36	183.95	2.18 ✓	4.44 ✓	40.45	1.18
183.95	186.75	1.65 ✓	3.30 ✓	30.17	.88
186.75	189.74	.83 ✓	2.40 ✓	14.05	.41
189.74	192.79	1.23 ✓	2.10 ✓	19.20	.56
192.79	195.83	1.18 ✓	.96 ✓	9.94	.29
195.83	198.88	.25 ✓	.62 ✓	6.17	.18
198.88	201.93	.40 ✓	1.08 ✓	8.91	.26
201.93	204.98	.83 ✓	.94 ✓	13.03	.38
204.98	208.03	.43 ✓	.68 ✓	5.14	.15
208.03	211.07	.44 ✓	1.14 ✓	6.17	.18
211.07	214.12	.44 ✓	1.10 ✓	5.14	.15
214.12	217.17	.80 ✓	1.16 ✓	12.00	.35
217.17	218.85	2.48 ✓	5.82 ✓	34.28	1.06
218.85	219.91	N/A	N/A	N/A	-
219.91	221.89	.19 ✓	.33 ✓	1.03	.03
221.89	224.33	.22 ✓	.48 ✓	2.06	.06
224.33	226.92	1.37 ✓	2.65 ✓	20.23	.59
226.92	228.14	2.40 ✓	1.56 ✓	38.39	1.12
228.14	230.43	3.38 ✓	2.82 ✓	45.25	1.32
230.43	233.48	1.98 ✓	.92 ✓	25.37	.74
233.48	236.52	1.38 ✓	3.40 ✓	19.20	.56
236.52	239.57	1.02 ✓	1.80 ✓	15.08	.44
239.57	242.62	3.00 ✓	3.96 ✓	36.34	1.06
242.62	245.67	2.03 ✓	2.22 ✓	30.17	.88
245.67	246.89	.74 ✓	1.50 ✓	6.17	.18
246.89	258.01	N/A	N/A	N/A	-
258.01	261.06	.60 ✓	1.10 ✓	9.94	.29
261.06	262.74	.38 ✓	.61 ✓	7.20	.21
262.74	264.63	3.83 ✓	3.96 ✓	47.31	1.38
264.63	266.18	2.38 ✓	3.72 ✓	30.17	.88
266.18	268.56	4.73 ✓	5.40 ✓	65.47	1.91
268.56	270.60	.98 ✓	1.68 ✓	17.14	.50
270.60	273.56	.34 ✓	1.28 ✓	6.17	.18
273.56	277.67	1.20 ✓	1.42 ✓	23.31	.68
277.67	281.64	N/A	N/A	N/A	-
281.64	284.68	1.38 ✓	1.40 ✓	21.25	.62
284.68	288.86	N/A	N/A	N/A	-
288.86	291.45	1.14 ✓	1.48 ✓	22.28	.65
291.45	292.85	.12 ✓	.32 ✓	5.14	.15
292.85	295.96	4.13 ✓	3.96 ✓	45.25	1.32

0.28

HOLE NO: A-85

INTERVAL		ASSAYS				
FROM	TO	PB %	ZN %	AG GM/TON	AG OZ/TON	
295.96	299.31	1.22✓	1.54✓	16.11	.47	
299.31	302.82	2.78✓	2.82✓	36.34	1.06	
302.82	304.22	.07✓	.18✓	6.17	.18	
304.22	306.26	6.63✓	12.77✓	115.87	3.38	
306.26	338.08	N/A	N/A	N/A	-	
338.08	340.86	4.43✓	6.75✓	65.47	1.91	
340.86	343.81	5.25✓	6.96✓	65.47	1.91	
343.81	346.25	5.23✓	11.53✓	80.56	2.35	
346.25	347.47	4.85✓	7.48✓	64.45	1.88	
347.47	351.13	5.98✓	9.03✓	80.56	2.35	
351.13	352.35	4.54✓	7.68✓	55.53	1.62	
352.35	353.57	1.87✓	1.56✓	26.40	.77	
353.57	355.24	2.78✓	3.72✓	35.31	1.03	
355.24	356.98	2.45✓	3.00✓	38.39	1.12	
356.98	357.84	6.35✓	9.97✓	90.84	2.65	
357.84	360.58	9.10✓	17.13✓	142.60	4.16	
360.58	361.65	3.87✓	4.62✓	61.36	1.79	
361.65	366.52	N/A	N/A	N/A	-	
366.52	368.50	.43✓	.26✓	7.20	.21	
368.50	369.11	.65✓	1.13✓	14.05	.41	
369.11	390.78	N/A	N/A	N/A	-	
390.78	391.55	.63✓	1.06✓	8.91	.26	
391.55	392.43	5.12✓	3.96✓	50.73	1.48	
392.43	393.47	.95✓	.92✓	14.05	.41	
393.47	395.17	4.65✓	3.66✓	51.42	1.50	
395.17	430.99 400.69	N/A 2.78	N/A 2.76	N/A 35.30	1.03	
400.69	430.99	N/A	N/A	N/A		

SPECIFIC MODEL BUSINESS FORM 4

DIAMOND DRILL LOG MASTER FILE

HOLE NO: A-86 LATITUDE: 11680.81 AZIMUTH: 0.00
 DEPARTURE: 7027.70 DIP: -90.00
 ELEVATION: ~~1315.61~~ 1301.36 DJH

DIP TESTS:	DEPTH	DIP	AZIMUTH
	36.58 ✓	-89.00 ✓	237.20 ✓
	97.54 ✓	-89.00 ✓	288.50 ✓
	182.88 ✓	-81.00 ✓	129.20 ✓
	243.84 ✓	-85.00 ✓	155.50 ✓
	304.80 ✓	-71.00 ✓	141.50 ✓
	426.72	-76.00	140.50
	505.97	-74.00	138.50
			384.0 -76.0 133.5
			426.7 -74.0 141.5
			505.9 -71.0 139.5

+topari

INTERVAL		ASSAYS			
FROM	TO	PB %	ZN %	AG GM/TON	AG 02/TON
0.00	376.58	N/A	N/A	N/A	-
376.58	379.78	.43 ✓	.33 ✓	4.11	.12
379.78	380.85	2.25 ✓	3.48 ✓	30.17	.88
380.85	383.07	2.08 ✓	4.14 ✓	31.19	.91
383.07	384.60	1.58 ✓	2.70 ✓	23.31	.68
384.60	386.00	1.78 ✓	3.18 ✓	25.37	.74
386.00	387.10	1.65 ✓	2.94 ✓	24.34	.71
387.10	388.96	1.60 ✓	4.62 ✓	21.25	.62
388.96	391.88	N/A	N/A	N/A	-
391.88	393.34	N/A	N/A	N/A	-
393.34	393.95	N/A	N/A	N/A	-
393.95	398.07	N/A	N/A	N/A	-
398.07	508.80	N/A	N/A	N/A	-
508.80	509.72	3.75 ✓	4.68 ✓	34.28	1.00
509.72	616.31	N/A	N/A	N/A	-

1301.36

1290.75
 10.61
 1301.36

HOLE NO: A-87 LATITUDE: 10996.26 AZIMUTH: 0.00
 HOLE LENGTH: 426.42 DEPARTURE: 7473.74 DIP: -90.00
 ELEVATION: 1315.61

DIP TESTS:	DEPTH	DIP	AZIMUTH
	60.96 ✓	-90.00 ✓	0.00 ✓
	121.92 ✓	-81.30 ✓	132.20 ✓
	176.78 ✓	-80.00 ✓	137.20 ✓
	243.84 ✓	-83.00 ✓	127.20 ✓
	304.48 ✓	-82.30 ✓	157.20 ✓
	353.57 ✓	-81.00 ✓	157.20 ✓

INTERVAL		ASSAYS				AG
FROM	TO	PB %	ZN %	AG GM/TON	AG 02/TON	
0.00	163.07	N/A	N/A	N/A	-	
163.07	163.62	.45 ✓	.76 ✓	8.91	.26	
163.62	165.05	5.37 ✓	9.26 ✓	81.59	2.38	
165.05	165.69	4.35 ✓	5.60 ✓	70.62	2.06	
165.69	166.42	2.93 ✓	3.12 ✓	45.25	7.32	
166.42	168.92	.89 ✓	1.02 ✓	15.08	.44	
168.92	169.93	2.05 ✓	3.60 ✓	27.42	.80	
169.93	170.99	3.15 ✓	2.58 ✓	40.45	1.18	
170.99	173.74	1.15 ✓	3.96 ✓	20.23	.59	
173.74	176.36	.43 ✓	.78 ✓	7.20	.21	
176.36	178.16	.10 ✓	.15 ✓	2.06	.06	
178.16	178.70	.62 ✓	.58 ✓	15.08	.44	
178.70	179.65	3.45 ✓	5.64 ✓	55.53	1.62	
179.65	183.43	N/A	N/A	N/A	-	
183.43	186.45	1.10 ✓	2.28 ✓	18.17	.53	
186.45	189.49	N/A	N/A	N/A	-	
189.49	192.33	2.03 ✓	3.30 ✓	28.45	.83	
192.33	194.71	.95 ✓	1.20 ✓	15.08	.44	
194.71	196.23	1.40 ✓	1.04 ✓	20.23	.59	
196.23	197.82	.62 ✓	.44 ✓	8.91	.26	
197.82	199.22	.93 ✓	.84 ✓	12.00	.35	
199.22	202.20	3.00 ✓	4.26 ✓	41.48	1.21	
202.20	203.00	2.00 ✓	2.22 ✓	26.40	.77	
203.00	206.04	3.08 ✓	3.90 ✓	43.54	1.27	
206.04	209.09	1.30 ✓	2.46 ✓	19.20	.56	
209.09	211.23	1.13 ✓	2.34 ✓	20.23	.59	
211.23	212.48	1.48 ✓	3.12 ✓	22.28	.65	
212.48	215.34	1.25 ✓	2.85 ✓	19.20	.56	
215.34	217.78	1.23 ✓	2.46 ✓	21.25	.62	
217.78	219.88	1.28 ✓	2.88 ✓	21.25	.62	
219.88	222.81	3.90 ✓	3.48 ✓	75.76	2.21	
222.81	225.70	2.38 ✓	6.66 ✓	42.51	1.24	
225.70	227.69	.07 ✓	.11 ✓	2.06	.06	
227.69	229.67	.17 ✓	.16 ✓	3.09	.09	
229.67	231.95	4.20 ✓	8.36 ✓	75.76	2.21	
231.95	233.48	2.08 ✓	7.26 ✓	45.25	1.32	
233.48	234.79	N/A	N/A	N/A	-	
234.79	235.98	3.15 ✓	7.61 ✓	38.39	1.12	
235.98	237.29	N/A	N/A	N/A	-	
237.29	239.27	7.33 ✓	14.54 ✓	112.44	3.28	
239.27	240.18	.55 ✓	2.34 ✓	13.03	.38	
240.18	249.05	N/A	N/A	N/A	-	

HOLE NO: A-87

INTERVAL		ASSAYS			
FROM	TO	PB %	ZN %	AG GM/TON	AG OZ/TON
249.05	250.58	3.68✓	4.68✓	56.56	1.65
250.58	253.78	1.20✓	1.52✓	12.00	.35
253.78	254.84	.75✓	1.04✓	10.97	.32
254.84	312.45	N/A	N/A	N/A	-
312.45	313.40	.63✓	.34✓	15.08	.44
313.40	316.96	1.73✓	2.88✓	32.22	.94
316.96	317.66	2.20✓	3.54✓	37.37	1.09
317.66	319.43	4.13✓	6.15✓	82.61	2.41
319.43	320.89	4.80✓	7.70✓	111.07	3.24
320.89	322.66	3.15✓	5.16✓	52.45	1.53
322.66	322.97	2.78✓	.50✓	50.39	1.47
322.97	323.70	N/A	N/A	N/A	-
323.70	324.06	.38✓	.12✓	14.05	.41
324.06	326.93	4.28✓	5.28✓	71.65	2.09
326.93	327.54	.73✓	.28✓	21.25	.62
327.54	328.85	N/A	N/A	N/A	-
328.85	330.56	5.71✓	6.48✓	85.70	2.50
330.56	331.93	4.58✓	7.68✓	72.67	2.12
331.93	334.98	4.73✓	8.48✓	85.70	2.50
334.98	336.96	4.65✓	10.07✓	95.64	2.79
336.96	337.63	.75✓	1.42✓	14.05	.41
337.63	347.84	N/A	N/A	N/A	-
347.84	350.22	1.10✓	1.88✓	30.17	.88
350.22	351.01	N/A	N/A	N/A	-
351.01	351.74	3.68✓	3.18✓	53.48	1.56
351.74	394.38	N/A	N/A	N/A	-
394.38	395.57	6.02✓	8.71✓	47.31	1.38
395.57	426.42	N/A	N/A	N/A	-

SHEET NO MOORE BUSINESS FORMS 4

HOLE NO: A-88 LATITUDE: 10827.58 AZIMUTH: 0.00
 HOLE LENGTH: 340.77 DEPARTURE: 7649.82 DIP: -90.00
 ELEVATION: 1313.97

DIP TESTS: DEPTH DIP AZIMUTH

	60.96✓	-89.00 ✓	121.20✓
121.9	131.92	-86.00 ✓	118.20 49.5
	182.88✓	-87.30✓	122.00✓
	256.03✓	-83.00 ✓	115.00 55.0
	316.99✓	-79.00✓	111.00 106.0

tropari

INTERVAL		ASSAYS				
FROM	TO	PB %	ZN %	AG GM/TON	AG OZ/TON	
0.00	116.43	N/A	N/A	N/A	-	
116.43	118.11	5.70	9.55	79.53	2.32	
118.11	120.09	2.00	3.90	22.28	.65	
120.09	122.22	1.50	2.46	18.17	.53	
122.22	125.27	1.58	2.40	16.11	.47	
125.27	127.10	1.04	3.84	21.25	.62	
127.10	128.78	1.23	2.46	20.23	.59	
128.78	129.54	N/A	N/A	N/A	-	
129.54	129.94	1.65	3.09	25.37	.74	
129.94	133.96	N/A	N/A	N/A	-	
133.96	135.33	.98	2.34	26.05	.76	
135.33	135.94	4.05	7.44	85.70	2.50	
135.94	138.23	1.18	1.48	26.40	.77	
138.23	140.82	6.19	12.44	93.93	2.74	
140.82	143.26	5.03	9.84	80.56	2.35	
143.26	146.30	2.70	6.00	41.48	1.21	
146.30	147.83	2.38	5.40	38.39	1.12	2.28
147.83	150.57	1.33	3.12	28.45	.83	
150.57	153.31	2.06	4.14	43.54	1.27	
153.31	156.36	2.05	4.56	44.56	1.30	
156.36	157.43	2.08	4.56	43.54	1.27	
157.43	157.73	.33	.83	4.11	.12	
157.73	160.93	N/A	N/A	N/A	-	
160.93	161.24	3.00	6.67	47.31	1.38	
161.24	165.60	N/A	N/A	N/A	-	
165.60	167.03	2.78	5.26	40.45	1.18	
167.03	169.47	2.00	4.74	39.42	1.15	
169.47	170.54	2.74	4.20	45.25	1.32	
170.54	176.78	N/A	N/A	N/A	-	
176.78	178.61	4.28	4.14	72.67	2.12	
178.61	197.82	N/A	N/A	N/A	-	
197.82	199.03	5.03	10.50	96.67	2.82	
199.03	200.25	5.33	11.65	98.38	2.87	
200.25	200.86	N/A	N/A	N/A	-	
200.86	201.17	1.85	2.58	30.17	.88	
201.17	204.06	N/A	N/A	N/A	-	
204.06	204.83	4.28	6.55	57.59	1.68	
204.83	205.74	5.68	8.77	80.56	2.35	
205.74	208.03	7.87	10.83	103.87	3.03	
208.03	208.79	5.03	5.40	57.59	1.68	
208.79	209.40	N/A	N/A	N/A	-	
209.40	210.01	5.64	6.24	67.53	1.97	
210.01	210.71	N/A	N/A	N/A	-	

SPECIAL TO MOORE BUSINESS FORMS 4

HOLE NO: A-88

INTERVAL		ASSAYS			
FROM	TO	PB %	ZN %	AG GM/TON	AG 02/TON
210.71	211.23	3.08✓	3.35✓	40.45	1.18
211.23	212.14	.95✓	.86✓	10.97	.32
212.14	214.34	1.78✓	1.44✓	25.37	.74
214.34	215.80	7.51✓	13.31✓	159.40	4.65
215.80	217.93	8.30✓	14.13✓	126.15	3.68
217.93	220.25	4.28✓	6.00✓	63.42	1.85
220.25	221.74	3.45✓	4.74✓	54.51	1.59
221.74	222.81	1.25✓	1.86✓	15.08	.44
222.81	224.03	.56✓	.72✓	10.97	.32
224.03	276.00	N/A	N/A	N/A	-
276.00	276.94	3.75✓	6.76✓	51.42	1.50
276.94	278.59	.01✓	.06✓	1.03	.03
278.59	286.21	N/A	N/A	N/A	-
286.21	286.82	.28✓	.46✓	3.09	.09
286.82	289.56	2.28✓	2.79✓	25.37	.74
289.56	299.01	N/A	N/A	N/A	-
299.01	299.92	.74✓	1.54✓	9.94	.29
299.92	301.14	3.83✓	5.59✓	49.36	1.44
301.14	302.36	.25✓	.40✓	4.11	.12
302.36	302.97	2.78✓	4.80✓	44.22	1.29
302.97	304.19	5.18✓	7.42✓	75.76	2.21
304.19	305.17	.88✓	.91✓	15.08	.44
305.17	305.56	2.48✓	3.24✓	36.34	1.06
305.56	306.32	1.65✓	2.63✓	30.17	.88
306.32	307.85	.60✓	.24✓	9.94	.79
307.85	309.22	1.50✓	.54✓	16.11	.47
309.22	310.29	4.88✓	3.00✓	49.36	1.44
310.29	310.90	.28✓	.40✓	8.91	.26
310.90	313.64	1.14✓	.94✓	20.23	.59
313.64	314.86	N/A	N/A	N/A	-
314.86	317.60	.13✓	.12✓	4.11	.12
317.60	319.13	.09✓	.20✓	3.09	.09
319.13	327.36	N/A	N/A	N/A	-
327.36	329.18	.13✓	.37✓	4.11	.12
329.18	340.77	N/A	N/A	N/A	-

SPEED-TO-MOORE BUSINESS FORMS 4

HOLE NO: A-89 LATITUDE: 11046.47 AZIMUTH: 0.00
 HOLE LENGTH: 378.00 DEPARTURE: 7515.27 DIP: -90.00
 ELEVATION: 1315.36

DIP TESTS: DEPTH ~~-90.0~~ DIP ~~0.0~~ AZIMUTH
Cal. 0 ~~39.48~~ ~~-89.00~~ ~~62.50~~
 109.73 ✓ -86.00 ✓ 98.50 ✓
 188.98 ✓ -85.00 ✓ 213.50 ✓

INTERVAL		ASSAYS				
FROM	TO	PB %	ZN %	AG GM/TON	AG 02/TON	
0.00	94.92	N/A	N/A	N/A	-	
94.92	95.40	.83 ✓	2.46 ✓	9.94	.29	
95.40	96.32	2.18 ✓	5.80 ✓	35.31	1.03	
96.32	96.62	3.08 ✓	4.14 ✓	43.54	1.27	
96.62	97.84	2.43 ✓	4.32 ✓	38.39	1.12	
97.84	99.15	2.67 ✓	3.24 ✓	40.45	1.18	
99.15	100.63	1.93 ✓	3.48 ✓	32.22	.94	
100.63	102.02	1.65 ✓	3.06 ✓	24.34	.71	
102.02	142.96	N/A	N/A	N/A	-	
142.96	143.33	4.50 ✓	7.78 ✓	74.73	2.18	
143.33	144.27	2.35 ✓	2.70 ✓	51.42	1.50	
144.27	145.69	4.20 ✓	3.18 ✓	50.39	1.47	
145.69	148.09	4.50 ✓	6.79 ✓	56.56	1.65	
148.09	149.02	3.15 ✓	5.44 ✓	46.28	1.35	
149.02	151.20	1.15 ✓	2.10 ✓	16.11	.47	
151.20	152.54	.60 ✓	1.22 ✓	8.91	.26	
152.54	155.11	.88 ✓	1.05 ✓	12.00	.35	
155.11	156.86	N/A	N/A	N/A	-	
156.86	157.51	3.23 ✓	6.60 ✓	45.25	1.32	
157.51	162.21	N/A	N/A	N/A	-	
162.21	163.78	3.90 ✓	7.44 ✓	65.47	1.91	
163.78	165.51	.93 ✓	1.74 ✓	15.08	.44	
165.51	168.01	1.13 ✓	1.14 ✓	22.28	.65	
168.01	178.69	N/A	N/A	N/A	-	
178.69	180.34	4.65 ✓	7.55 ✓	80.56	2.35	
180.34	180.66	N/A	N/A	N/A	-	
180.66	182.03	3.60 ✓	5.76 ✓	50.39	1.47	
182.03	259.90	N/A	N/A	N/A	-	
259.90	260.70	5.03 ✓	9.50 ✓	72.67	2.12	
260.70	269.80	N/A	N/A	N/A	-	
269.80	272.00	5.75 ✓	9.32 ✓	93.93	2.74	
272.00	280.80	N/A	N/A	N/A	-	
280.80	281.55	2.85 ✓	7.22 ✓	48.33	1.41	
281.55	281.90	N/A	N/A	N/A	-	
281.90	282.75	3.60 ✓	6.22 ✓	59.30	1.73	
282.75	283.30	N/A	N/A	N/A	-	
283.30	285.00	2.45 ✓	6.83 ✓	43.54	1.27	
285.00	288.40	1.93 ✓	3.24 ✓	28.45	.83	
288.40	291.30	3.90 ✓	3.36 ✓	50.39	1.47	
291.30	291.80	1.08 ✓	.90 ✓	19.20	.56	
291.80	293.30	N/A	N/A	N/A	-	
293.30	294.90	1.43 ✓	1.16 ✓	18.17	.53	
294.90	296.00	N/A	N/A	N/A	-	
296.00	297.30	5.40 ✓	7.38 ✓	85.70	2.50	
297.30	342.80	N/A	N/A	N/A	-	

SPEED TO MOVE BUSINESS FORMS 4

HOLE NO: A-90 LATITUDE: 10874.36 AZIMUTH: 0.00
 HOLE LENGTH: 316.40 DEPARTURE: 7692.18 DIP: -90.00
 ELEVATION: 1312.72

DIP TESTS: DEPTH DIP AZIMUTH

	60.96✓	-89.00✓	59.50✓	
	121.92✓	-79.00✓	109.50✓	
	182.88✓	-72.00✓	91.20✓	DEPTH DIP AZ.
	243.84✓	-69.00	78.50	304.8 -69.0 79.5
		-75.0	93.5	

INTERVAL		ASSAYS			AG
FROM	TO	PB %	ZN %	AG GM/TON	AG OZ/TON
0.00	49.25	N/A	N/A	N/A	-
49.25	51.65	2.40✓	5.16✓	41.48	1.21
51.65	53.65	.13	1.08✓	2.06	.06
53.65	56.50	1.45✓	3.90✓	26.40	.77
56.50	57.67	N/A	N/A	N/A	-
57.67	61.50	1.88✓	4.44✓	31.19	.91
61.50	62.40	N/A	N/A	N/A	-
62.40	63.30	2.08✓	5.04✓	34.28	1.00
63.30	63.67	N/A	N/A	N/A	-
63.67	64.70	1.50✓	3.72✓	25.37	.74
64.70	66.50	1.48✓	3.42✓	24.34	.71
66.50	68.45	N/A	N/A	N/A	-
68.45	69.77	1.18✓	1.58✓	15.08	.44
69.77	70.20	N/A	N/A	N/A	-
70.20	72.50	.87✓	1.64✓	17.14	.50
72.50	77.39	N/A	N/A	N/A	-
77.39	79.05	4.60✓	7.56✓	61.36	1.79
79.05	79.90	.70✓	1.82✓	12.00	.35
79.90	82.65	7.43✓	10.70✓	110.04	3.21
82.65	84.70	1.68✓	5.40✓	25.37	.74
84.70	86.95	2.18✓	5.04✓	38.39	1.12
86.95	88.90	3.45✓	6.60✓	44.22	1.29
88.90	90.00	1.88✓	1.88✓	20.23	.59
90.00	91.00	2.38✓	2.46	34.28	1.00
91.00	92.00	4.35✓	7.08✓	66.50	1.94
92.00	93.00	5.11✓	6.13✓	76.79	2.24
93.00	93.95	3.60✓	4.08✓	50.39	1.47
93.95	94.60	3.83	8.72✓	60.33	1.76
94.60	94.85	4.13✓	9.60✓	71.65	2.09
94.85	96.40	.35✓	.40✓	5.14	.15
96.40	98.50	3.75✓	5.52✓	60.33	1.76
98.50	99.50	3.23✓	4.14✓	44.56	1.30
99.50	101.95	N/A	N/A	N/A	-
101.95	104.00	3.12✓	5.52✓	44.22	1.29
104.00	105.00	5.88✓	9.51✓	85.01	2.48
105.00	106.00	4.28✓	8.50✓	54.51	1.59
106.00	107.00	8.91✓	15.64✓	125.12	3.65
107.00	108.00	6.94✓	13.67✓	103.87	3.03
108.00	206.00	N/A	N/A	N/A	-
206.00	207.00	4.69✓	6.05✓	90.84	2.65
207.00	213.30	N/A	N/A	N/A	-
213.30	214.60	4.80✓	7.83✓	62.39	1.82
214.60	215.40	7.50✓	12.32✓	100.78	2.94
215.40	216.20	3.19✓	5.04✓	45.25	1.32

STER FILE

HOLE NO: A-90

INTERVAL		ASSAYS			
FROM	TO	PB %	ZN %	AG GM/TON	
216.20	216.80	1.78 ✓	3.36 ✓	25.37	AG 02/TON 74
216.80	218.20	1.68 ✓	3.06 ✓	20.23	.59
218.20	264.70	N/A	N/A	N/A	—
264.70	266.00	4.50 ✓	5.28 ✓	56.56	1.65
266.00	267.50	1.00 ✓	.72 ✓	13.03	.38
267.50	268.70	2.50 ✓	3.60 ✓	37.37	1.09
268.70	269.80	.35 ✓	.29 ✓	8.23	.24
269.80	271.00	10.80 ✓	5.88 ✓	107.98	3.15
271.00	271.90	5.20 ✓	3.54 ✓	60.33	1.76
271.90	273.10	4.13 ✓	4.98 ✓	59.30	1.73
273.10	316.40	N/A	N/A	N/A	—

HOLE NO: A-91 LATITUDE: 11720.80 AZIMUTH: 0.00
 HOLE LENGTH: 539.80 DEPARTURE: 6899.62 DIP: -90.00
 ELEVATION: 1300.15

DIP TESTS:	DEPTH	DIP	AZIMUTH
	30.48✓	-87.30✓	72.20 ✓
	91.44✓	-86.00 ✓	81.20 ✓
	213.36✓	-81.20 ✓	84.20 ✓
	335.28✓	-78.00✓	112.20 ✓
	396.24✓	-78.00✓	105.20 ✓
	518.16✓	-83.00✓	58.20 ✓

INTERVAL		ASSAYS			
FROM	TO	PB %	ZN %	AG GM/TON	
0.00	398.90	N/A	N/A	N/A	AG 02/TON
398.90	400.70	1.00 ✓	1.54 ✓	12.00	.35
400.70	402.50	N/A	N/A	N/A	-
402.50	405.00	1.48 ✓	2.94 ✓	14.05	.41
405.00	539.80	N/A	N/A	N/A	-

HOLE NO: A-92 LATITUDE: 10916.45 AZIMUTH: 0.00
 HOLE LENGTH: 288.65 DEPARTURE: 7734.46 DIP: -90.00
 ELEVATION: 1311.54

DIP TESTS:	DEPTH	DIP	AZIMUTH
	60.96✓	-86.00✓	30.20✓
	121.92✓	-76.00✓	92.20✓
	182.88✓	-70.00✓	85.40✓
	262.13✓	-64.00✓	81.20✓

INTERVAL		ASSAYS				
FROM	TO	PB	ZN	AG	AG	
		%	%	GM/TON	OZ/TON	
0.00	49.40	N/A	N/A	N/A	-	
49.40	50.30	2.08✓	3.42✓	41.48	1.21	
50.30	51.20	3.75✓	4.92✓	50.39	1.47	
51.20	52.40	5.73✓	4.02✓	69.59	2.03	
52.40	53.90	10.65✓	16.76✓	157.35	4.59	
53.90	54.90	8.62✓	14.07✓	121.01	3.53	
54.90	55.80	3.98✓	7.22✓	63.42	1.85	
55.80	56.70	5.63✓	11.01✓	86.73	2.53	
56.70	189.60	N/A	N/A	N/A	-	
189.60	190.50	5.58✓	7.04✓	81.59	2.38	
190.50	191.50	3.68✓	5.48✓	54.51	1.59	
191.50	192.50	8.12✓	7.55✓	114.84	3.35	
192.50	193.30	6.78✓	5.28✓	90.84	2.65	
193.30	194.30	.70✓	.70✓	9.94	.29	
194.30	288.60	N/A	N/A	N/A	-	

SHEET/FILE MOORE BUSINESS FORMS 4

HOLE NO: A-93 LATITUDE: 11085.29 AZIMUTH: 0.00
 HOLE LENGTH: 350.52 DEPARTURE: 7558.80 DIP: -90.00
 ELEVATION: 1313.38

DIP TESTS:	DEPTH	DIP	AZIMUTH
	60.96✓	-85.00✓	118.20✓
	121.92✓	-79.00✓	111.20✓
	195.07✓	-74.00✓	123.20✓
	262.13✓	-72.30✓	115.20✓
	338.33✓	-78.00✓	57.48✓

INTERVAL		ASSAYS				
FROM	TO	PB %	ZN %	AG GM/TON	AG OZ/TON	
0.00	76.60	N/A	N/A	N/A	-	
76.60	78.50	2.03✓	4.94✓	37.37	1.09	
78.50	79.10	N/A	N/A	N/A	-	
79.10	81.90	2.50✓	5.04	43.54	1.27	
81.90	82.30	N/A	N/A	N/A	-	
82.30	83.60	.28✓	.42	8.91	.26	
83.60	87.50	.62✓	1.02	12.00	.35	
87.50	106.40	N/A	N/A	N/A	-	
106.40	109.70	.83✓	2.00	16.11	.47	
109.70	112.80	1.33✓	2.58	22.28	.65	
112.80	139.30	N/A	N/A	N/A	-	
139.30	140.80	1.78✓	1.70✓	27.42	.80	
140.80	142.00	N/A	N/A	N/A	-	
142.00	143.60	4.50✓	8.49✓	71.65	2.09	
143.60	288.80	N/A	N/A	N/A	-	
288.80	290.80	4.88✓	4.56✓	75.76	2.21	
290.80	298.40	N/A	N/A	N/A	-	
298.40	300.90	.88✓	1.62✓	13.03	.38	
300.90	302.10	1.43✓	3.30✓	21.25	.62	
302.10	302.70	3.38✓	5.88✓	57.59	1.68	
302.70	303.50	N/A	N/A	N/A	-	
303.50	304.60	1.43✓	1.70✓	21.25	.62	
304.60	350.50	N/A	N/A	N/A	-	

HOLE NO: A-94 LATITUDE: 11770.72 AZIMUTH: 0.00
 HOLE LENGTH: 301.14 DEPARTURE: 7111.62 DIP: -90.00
 ELEVATION: 1309.63

DIP TESTS:	DEPTH	DIP	AZIMUTH
	30.48 ✓	-87.00 ✓	76.20 ✓
	91.44 ✓	-83.30 ✓	80.20 ✓
	152.40 ✓	-82.30 ✓	96.20 ✓
	213.36 ✓	-81.00 ✓	87.20 ✓
	274.32 ✓	-83.30 ✓	190.20 ✓

INTERVAL		ASSAYS		
FROM	TO	PB	ZN	AG
		%	%	GM/TON
0.00	301.10	N/A	N/A	N/A

SPECFILO MOORE BUSINESS FORMS 4

HOLE NO: A-95 LATITUDE: 10828.04 AZIMUTH: 0.00
 HOLE LENGTH: 213.40 DEPARTURE: 7735.68 DIP: -90.00
 ELEVATION: 1313.41

DIP TESTS: DEPTH DIP AZIMUTH
 73.15 ✓ -89.00 ✓ 82.20 ✓
 134.11 ✓ -76.00 ✓ 103.20 ✓
 195.07 ✓ -88.00 ✓ 88.20 ✓
 -69.2

INTERVAL		ASSAYS				
FROM	TO	PB %	ZN %	AG GM/TON	AG OZ/TON	
0.00	57.00	N/A	N/A	N/A	-	
57.00	57.90	5.33 ✓	9.90 ✓	74.73	2.18	
57.90	58.80	10.50 ✓	16.61 ✓	173.46	5.06	
58.80	60.40	3.15 ✓	4.50 ✓	49.36	1.44	
60.40	61.60	2.03 ✓	2.58 ✓	36.34	1.06	
61.60	63.40	3.83 ✓	6.48 ✓	60.33	1.76	
63.40	66.00	5.55 ✓	8.53 ✓	79.19	2.31	
66.00	213.40	N/A	N/A	N/A	-	

SPECIAL ORDER BUSINESS FORMS 4

DIAMOND DRILL LOG MASTER FILE

HOLE NO: A-96 LATITUDE: 10744.23 AZIMUTH: 0.00
 DEPARTURE: 7737.63 DIP: -90.00
 ELEVATION: 1303.59

DIP TESTS: DEPTH DIP AZIMUTH
 49.07 -88.00 106.00
 103.94 -86.00 105.00

INTERVAL		ASSAYS				AG
FROM	TO	PB %	ZN %	AG GM/TON	AG 02/TON	
0.00	49.40	N/A	N/A	N/A	-	
49.40	53.10	1.03✓	2.10✓	18.17	.53	
53.10	56.70	2.50✓	3.66✓	32.22	.94	
56.70	57.70	3.68✓	6.00✓	54.51	1.59	
57.70	58.70	1.83✓	5.88✓	25.37	.74	
58.70	59.70	N/A	N/A	N/A	-	
59.70	62.20	2.78✓	5.88✓	45.25	1.32	
62.20	63.40	3.45✓	6.93✓	56.56	1.65	
63.40	66.10	2.43✓	5.64✓	35.31	1.03	
66.10	68.30	3.15✓	10.52✓	54.51	1.59	
68.30	69.80	1.68✓	8.30✓	33.25	.97	
69.80	89.30	N/A	N/A	N/A	-	
89.30	92.40	2.15✓	4.44✓	33.25	.97	
92.40	94.10	3.08✓	6.70✓	45.25	1.32	
94.10	94.60	8.37✓	23.93✓	154.95	4.52	
94.60	134.40	N/A	N/A	N/A	-	
134.40	135.30	6.67✓	11.39✓	112.10	3.27	
135.30	136.90	9.61✓	13.15✓	111.07	3.24	
136.90	139.30	10.27✓	16.58✓	152.20	4.44	
139.30	142.30	8.97✓	17.28✓	141.23	4.12	
142.30	143.30	7.88✓	18.33✓	115.87	3.38	
143.30	145.10	9.87✓	23.51✓	138.49	4.04	
145.10	146.30	7.20✓	20.30✓	126.15	3.68	
146.30	148.40	6.00✓	14.13✓	98.73	2.88	
148.40	149.10	9.63✓	22.37✓	177.57	5.18	
149.10	150.30	7.53✓	17.61✓	125.12	3.65	
150.30	151.50	7.20✓	17.92✓	142.26	4.15	

D I A M O N D D R I L L L O G M A S T E R F I L E

HOLE NO: A-97 LATITUDE: 12183.75 AZIMUTH: 0.00
 DEPARTURE: 6688.70 DIP: -90.00
 ELEVATION: 1315.77

INTERVAL		ASSAYS			
FROM	TO	PB	ZN	AG	AG
		%	%	GM/TON	GM/TON
0.00	19.10	N/A	N/A	N/A	-
19.10	20.40	1.40 ✓	1.54 ✓	30.17	.88
20.40	22.40	.50 ✓	.38 ✓	30.17	.88
22.40	23.50	.10 ✓	.18 ✓	8.23	.24
23.50	99.97	N/A	N/A	N/A	-

MOORE SPECIFIC 4

HOLE NO: A-98 LATITUDE: 12141.45 AZIMUTH: 0.00
 HOLE LENGTH: 145.50 DEPARTURE: 6642.05 DIP: -90.00
 ELEVATION: 1316.20

DIP TESTS: DEPTH DIP AZIMUTH
 24.38 ✓ -89.00 ✓ 0.20 ✓
 60.96 ✓ -87.00 ✓ 1.20 ✓
 121.92 ✓ -86.00 ✓ 303.00 ✓

INTERVAL		ASSAYS			
FROM	TO	PB %	ZN %	AG GM/TON	
0.00	24.20	N/A	N/A	N/A	AG 02/TON
24.20	26.80	2.70 ✓	2.64 ✓	35.31	1.03 ✓
26.80	145.50	N/A	N/A	N/A	

HOLE NO: A-99 LATITUDE: 10657.97 AZIMUTH: 0.00
 HOLE LENGTH: 189.60 DEPARTURE: 7821.61 DIP: -90.00
 ELEVATION: 1296.41

DIP TESTS: DEPTH DIP AZIMUTH
 60.96 ✓ -85.00 ✓ 72.00 ✓
 115.82 ✓ -75.00 ✓ 77.00 ✓
 176.78 ✓ -72.00 ✓ 75.00 ✓

INTERVAL		ASSAYS				AG
FROM	TO	PB	ZN	AG		AG
		%	%	GM/TON		OZ/TON
0.00	62.40	N/A	N/A	N/A		-
62.40	64.00	1.33 ✓	4.38 ✓	21.25		.62
64.00	138.50	N/A	N/A	N/A		-
138.50	139.50	4.50 ✓	5.04 ✓	65.47		1.91
139.50	140.50	N/A	N/A	N/A		-
140.50	141.60	8.08 ✓	7.35 ✓	96.67		2.82
141.60	142.30	2.43 ✓	5.40 ✓	41.48		1.21
142.30	143.90	3.83 ✓	4.38 ✓	40.45		1.18
143.90	145.40	3.08 ✓	4.32 ✓	41.48		1.21
145.40	147.50	2.30 ✓	3.30 ✓	30.17		.88
147.50	150.20	5.63 ✓	7.43 ✓	74.73		2.18
150.20	152.50	4.73 ✓	7.84 ✓	70.62		2.06
152.50	153.20	3.00 ✓	3.96 ✓	45.25		1.32
153.20	154.20	6.90 ✓	10.31 ✓	101.81		2.97
154.20	155.90	1.93 ✓	1.08 ✓	31.19		.91
155.90	157.60	.95 ✓	.34 ✓	16.11		.47
157.60	160.60	.23 ✓	.16 ✓	8.91		.26
160.60	163.70	.13 ✓	.08 ✓	7.20		.21
163.70	166.40	.33 ✓	.54 ✓	10.97		.32
166.40	170.40	1.43 ✓	1.00 ✓	22.28		.65
170.40	173.40	.23 ✓	.58 ✓	6.17		.18
173.40	176.80	.78 ✓	1.34 ✓	9.94		.29
176.80	178.30	.35 ✓	.66 ✓	6.17		.18
178.30	181.70	.20 ✓	.34 ✓	1.03		.03
181.70	189.60	N/A	N/A	N/A		-

HOLE NO: A-100 LATITUDE: 10788.73 AZIMUTH: 0.00
 HOLE LENGTH: 250.55 DEPARTURE: 7780.36 DIP: -90.00
 ELEVATION: 1309.23

DIP TESTS: DEPTH DIP AZIMUTH
 67.05✓ -86.00✓ 303.00 ✓
 121.92✓ -83.00✓ 58.00 ✓
 182.88✓ -73.00✓ 81.00 ✓
 225.55 (231.65) -71.00 ✓ 76.00 ✓

INTERVAL		ASSAYS				AG
FROM	TO	PB	ZN	AG		02/TON
		%	%	GM/TON		
0.00	65.40	N/A	N/A	N/A		-
65.40	66.20	10.35✓	10.50✓	176.54		5.15
66.20	67.40	N/A	N/A	N/A		-
67.40	68.70	11.55✓	12.29✓	176.54		5.15
68.70	68.90	N/A	N/A	N/A		-
68.90	70.10	3.00✓	4.62✓	39.42		1.15
70.10	71.20	N/A	N/A	N/A		-
71.20	73.50	11.10✓	11.11✓	153.23		4.47
73.50	81.30	N/A	N/A	N/A		-
81.30	82.80	6.68✓	9.17✓	103.87		3.03
82.80	88.80	N/A	N/A	N/A		-
88.80	89.60	8.25✓	8.46✓	115.87		3.38
89.60	90.90	N/A	N/A	N/A		-
90.90	92.20	9.45✓	9.23✓	130.95		3.82
92.20	93.40	4.13✓	4.14✓	59.30		1.73
93.40	94.10	.55✓	.96✓	8.23		.24
94.10	174.70	N/A	N/A	N/A		-
174.70	175.60	7.65✓	11.40✓	121.01		3.53
175.60	176.50	6.23✓	10.05✓	98.73		2.88
176.50	178.20	7.50✓	11.67✓	118.95		3.47
178.20	179.20	2.25✓	3.18✓	40.45		1.18
179.20	180.70	4.65✓	5.96✓	70.62		2.06
180.70	181.40	3.30✓	5.58✓	48.33		1.41
181.40	181.90	3.60✓	6.31✓	46.28		1.35
181.90	182.30	4.88✓	7.30✓	77.82		2.27
182.30	183.20	3.08✓	4.38✓	44.22		1.29
183.20	184.40	2.08✓	4.08✓	33.25		.97
184.40	185.40	2.93✓	4.38✓	48.33		1.41
185.40	250.50	N/A	N/A	N/A		-

SHEET 10 MOORE BUSINESS FORMS 4

HOLE NO: A-101 LATITUDE: 12050.85 AZIMUTH: 0.00
 HOLE LENGTH: 269.75 DEPARTURE: 6729.44 DIP: -90.00
 ELEVATION: 1314.99

DIP TESTS:	DEPTH	DIP	AZIMUTH
	60.96 ✓	-86.00 ✓	17.00 ✓
	121.92 ✓	-81.00 ✓	53.00 ✓
	213.36 ✓	-84.00 ✓	41.00 ✓
	256.03 ✓	-85.00 ✓	17.00 ✓

INTERVAL		ASSAYS		
FROM	TO	PB	ZN	AG
		%	%	GM/TON
0.00	269.70	N/A	N/A	N/A

HOLE NO: A-102 LATITUDE: 10575.30 AZIMUTH: 0.00
 HOLE LENGTH: 201.78 DEPARTURE: 7913.47 DIP: -90.00
 ELEVATION: 1289.92

DIP TESTS: DEPTH DIP AZIMUTH
 67.05 ✓ -85.00 ✓ 74.00 ✓
 128.02 ✓ -77.00 ✓ 67.00 ✓
 170.69 ✓ -79.30 ✓ 55.00 ✓

INTERVAL		ASSAYS				
FROM	TO	PB %	ZN %	AG GM/TON	AG OZ/TON	
0.00	137.10	N/A	N/A	N/A	-	
137.10	139.30	1.76 ✓	2.40 ✓	26.40	.77	
139.30	140.30	10.18 ✓	9.58 ✓	117.92	3.44	K
140.30	142.00	1.23 ✓	1.58 ✓	25.37	.74	
142.00	183.40	N/A	N/A	N/A	-	

HOLE NO: A-103 LATITUDE: 10532.37 AZIMUTH: 0.00
 HOLE LENGTH: 214.00 DEPARTURE: 7870.14 DIP: -90.00
 ELEVATION: 1288.27

DIP TESTS: DEPTH DIP AZIMUTH

51.82 ✓	-87.00 ✓	292.00 ✓
112.77 ✓	-83.00 ✓	77.00 ✓
182.88 ✓	-81.00 ✓	72.00 ✓

INTERVAL		ASSAYS			
FROM	TO	PB %	ZN %	AG GM/TON	AG OZ/TON
0.00	143.00	N/A	N/A	N/A	-
143.00	145.00	2.85 ✓	5.28 ✓	40.45	1.18
145.00	160.10	N/A	N/A	N/A	-
160.10	160.90	6.38 ✓	6.10 ✓	76.79	2.24
160.90	162.10	.15 ✓	.14 ✓	6.17	.18
162.10	163.80	3.00 ✓	5.50 ✓	21.25	.62
163.80	170.40	N/A	N/A	N/A	-
170.40	171.90	5.70 ✓	7.51 ✓	92.90	2.71
171.90	214.00	N/A	N/A	N/A	-

HOLE NO: A-104 LATITUDE: 11082.33 AZIMUTH: 0.00
 HOLE LENGTH: 420.30 DEPARTURE: 7473.48 DIP: -90.00
 ELEVATION: 1320.17

DIP TESTS:	DEPTH	DIP	AZIMUTH
✓60.96	-82.30✓	144.20✓	
✓121.92	-82.30✓	117.20	128.0
✓182.88	-80.30✓	131.20✓	
✓262.13	-77.00✓	142.20✓	
✓323.09	-80.00✓	152.20✓	
✓396.24	-76.00✓	145.20✓	

INTERVAL		ASSAYS			
FROM	TO	PB %	ZN %	AG GM/TON	AG O2/TON
0.00	103.10	N/A	N/A	N/A	-
103.10	104.70	2.00✓	3.30✓	34.28	1.00
104.70	105.20	N/A	N/A	N/A	-
105.20	107.70	1.98✓	3.90✓	30.17	.88
107.70	109.60	2.08✓	3.84✓	35.31	1.03
109.60	118.40	N/A	N/A	N/A	-
118.40	121.60	3.23✓	5.34✓	50.39	1.47
121.60	125.90	1.73✓	3.00✓	26.40	.77
125.90	128.00	1.43✓	3.00✓	20.23	.59
128.00	129.50	2.30✓	4.02✓	27.42	.80
129.50	132.70	1.98✓	4.08✓	37.37	1.09
132.70	133.90	1.15✓	2.28✓	18.17	.53
133.90	135.80	3.75✓	8.25✓	47.31	1.38
135.80	139.00	2.48✓	6.06✓	45.25	1.32
139.00	142.00	3.08✓	5.16✓	46.28	1.35
142.00	145.20	3.98✓	5.16✓	55.53	1.62
145.20	148.40	3.08✓	5.56✓	43.54	1.27
148.40	151.20	1.83✓	4.38✓	29.14	.85
151.20	153.10	.30✓	1.68✓	6.17	.18
153.10	156.90	1.80✓	1.81✓	27.42	.80
156.90	160.30	2.23✓	3.18✓	30.17	.88
160.30	161.30	N/A	N/A	N/A	-
161.30	163.70	2.63✓	2.76✓	40.45	1.18
163.70	166.70	3.00✓	5.04✓	44.22	1.29
166.70	169.10	1.88✓	4.02✓	33.25	.97
169.10	170.80	2.08✓	1.40✓	24.34	.71
170.80	173.40	.78✓	1.46✓	13.03	.38
173.40	176.60	N/A	N/A	N/A	-
176.60	178.80	1.48✓	1.78✓	21.25	.62
178.80	180.20	N/A	N/A	N/A	-
180.20	180.70	5.24✓	10.64✓	103.87	3.03
180.70	199.60	N/A	N/A	N/A	-
199.60	202.70	5.33✓	8.43✓	93.93	2.74
202.70	205.70	3.15✓	4.56✓	47.31	1.38
205.70	206.70	1.63✓	4.14✓	27.42	.80
206.70	362.20	N/A	N/A	N/A	-
362.20	364.80	.38✓	.37✓	8.23	.24
364.80	367.20	.34✓	.52✓	8.91	.26
367.20	368.00	.34✓	.66✓	9.94	.29
368.00	368.70	3.30✓	4.14✓	45.25	1.32
368.70	391.70	N/A	N/A	N/A	-
391.70	393.30	5.19✓	8.43✓	95.64	2.79

SPECIFIC MOORE BUSINESS FORMS 4

HOLE NO: A-105 LATITUDE: 10354.00 AZIMUTH: 0.00
 HOLE LENGTH: 199.60 DEPARTURE: 7698.85 DIP: -90.00
 ELEVATION: 1273.74

DIP TESTS: DEPTH DIP AZIMUTH
 60.96 ✓ -88.00 ✓ 192.00 ✓
 121.92 ✓ -89.00 ✓ 97.00 ✓
 182.88 ✓ -86.00 ✓ 65.00 ✓ *tropari*

INTERVAL		ASSAYS				
FROM	TO	PB %	ZN %	AG GM/TON	AG	
0.00	99.60	N/A	N/A	N/A	0.2/TON	
99.60	102.20	2.92 ✓	2.00 ✓	35.31	1.03	102.2-102.6 N/A
102.20	106.70	.52 ✓	.92 ✓	13.03	.38	
106.70	109.90	.19 ✓	.24 ✓	6.17	.18	
109.90	111.40	N/A	N/A	N/A	-	
111.40	112.90	.22 ✓	.36 ✓	5.14	.15	
112.90	114.80	5.97 ✓	6.45 ✓	82.61	2.41	
114.80	117.30	.19 ✓	.34 ✓	6.17	.18	
117.30	119.80	.27 ✓	.31 ✓	7.20	.21	
119.80	122.80	.12 ✓	.42 ✓	5.14	.15	
122.80	123.70	2.23 ✓	3.20 ✓	25.37	.74	
123.70	125.00	.23 ✓	.76 ✓	9.94	.29	
125.00	144.50	N/A	N/A	N/A	-	
144.50	146.00	3.00 ✓	2.30 ✓	40.45	1.18	
146.00	167.20	N/A	N/A	N/A	-	
167.20	168.40	3.45 ✓	3.00 ✓	41.48	1.21	
168.40	168.90	4.88 ✓	7.29 ✓	55.53	1.62	
168.90	171.30	.27 ✓	.21 ✓	9.94	.29	
171.30	173.50	.68 ✓	.71 ✓	16.11	.47	
173.50	174.30	4.58 ✓	3.66 ✓	57.59	1.68	
174.30	176.90	2.93 ✓	2.10 ✓	38.39	1.12	
176.90	199.60	N/A	N/A	N/A	-	

SPECIAL MOORE BUSINESS FORMS 4

HOLE NO: A-106
 HOLE LENGTH: 190.50

LATITUDE: 10741.58
 DEPARTURE: 7820.74
 ELEVATION: 1303.61

AZIMUTH: 0.00
 DIP: -90.00

DIP TESTS: DEPTH DIP AZIMUTH
 ✓97.54 ✓-84.00 ✓74.00 60.96 ~~8~~ -89.0 392.8
 ✓170.69 ✓78.00 ✓75.00

INTERVAL		ASSAYS					AG
FROM	TO	PB %	ZN %	AG GM/TON		02/TON	
0.00	46.80	N/A	N/A	N/A		-	
46.80	47.60	.80	7.80✓	8.83✓	110.04	3.21	
47.60	49.20	1.60	11.94✓	9.11✓	182.37	5.32	
49.20	50.30	1.10	.07✓	.10✓	.00	TR	
50.30	50.50	.20	6.48✓	14.49✓	49.36	1.44	
50.50	90.30		N/A	N/A	N/A	-	
90.30	91.40	1.10	6.79✓	6.37✓	97.70	2.85	
91.40	151.30		N/A	N/A	N/A	-	
151.30	153.80	2.50	5.48✓	8.28✓	97.70	2.85	
153.80	154.80	1.00	5.33✓	5.50✓	75.76	2.21	
154.80	157.20	2.40	7.82✓	9.00✓	100.78	2.94	
157.20	159.40	2.20	1.25✓	1.66✓	20.23	.59	
159.40	161.20	1.80	4.28✓	5.28✓	53.48	1.56	
161.20	164.00	2.80	1.28✓	2.22✓	23.31	.68	
164.00	168.50		N/A	N/A	N/A	-	
168.50	171.00	2.50	.22✓	.51✓	8.23	.24	
171.00	174.00	3.00	.27✓	.55✓	8.23	.24	
174.00	176.20	2.20	.24✓	.27✓	9.26	.27	
176.20	178.00	1.80	.20✓	.22✓	9.26	.27	
178.00	181.30	3.30	.27✓	.35✓	2.06	.06	
181.30	190.50		N/A	N/A	N/A	-	

SPECIAL TO MOORE BUSINESS FORMS 4

HOLE NO: A-107
 HOLE LENGTH: 216.71

LATITUDE: 10487.32
 DEPARTURE: 7828.25
 ELEVATION: 1286.46

AZIMUTH: 0.00
 DIP: -90.00

DIP TESTS: DEPTH DIP AZIMUTH
 73.15 ✓ -89.00 ✓ 286.00 ✓
 128.02 ✓ -87.00 ✓ 43.00 ✓
 207.26 ✓ -76.00 ✓ 44.00 ✓

INTERVAL		ASSAYS			AG GM/TON	AG 02/TON
FROM	TO	PB %	ZN %	AG		
0.00	52.40	N/A	N/A	N/A		
52.40	54.90	7.98 ✓	15.22 ✓	117.92	3.44	
54.90	55.50	.39 ✓	4.50 ✓	6.17	.18	
55.50	56.70	2.70 ✓	5.30 ✓	39.42	1.15	
56.70	58.50	4.88 ✓	9.27 ✓	63.42	1.85	
58.50	61.00	4.20 ✓	8.82 ✓	61.36	1.79	
61.00	62.90	6.76 ✓	11.70 ✓	80.56	2.35	
62.90	65.50	9.06 ✓	17.05 ✓	146.03	4.26	
65.50	67.80	7.72 ✓	15.26 ✓	103.87	3.03	
67.80	69.80	11.11 ✓	21.65 ✓	171.40	5.00	
69.80	71.30	6.89 ✓	13.66 ✓	111.07	3.24	
71.30	73.80	.40 ✓	1.20 ✓	13.03	.38	
73.80	76.20	.65 ✓	.90 ✓	9.94	.29	
76.20	79.20	.95 ✓	.93 ✓	15.08	.44	
79.20	82.00	.14 ✓	.35 ✓	5.14	.15	
82.00	84.70	.23 ✓	.31 ✓	9.94	.29	
84.70	87.50	.29 ✓	.84 ✓	8.91	.26	
87.50	90.50	.12 ✓	.42 ✓	8.23	.24	
90.50	93.50	N/A .58	N/A .86	N/A 15.08	.44	Sample 2439
93.50	96.60	.13 ✓	.31 ✓	8.23	.24	
96.60	99.10	.04 ✓	.42 ✓	7.20	.21	
99.10	102.40	.12 ✓	.65 ✓	9.94	.29	
102.40	105.20	.13 ✓	.40 ✓	9.94	.29	
105.20	108.20	.07 ✓	.15 ✓	6.17	.18	
108.20	110.60	.05 ✓	.12 ✓	5.14	.15	
110.60	112.20	.04 ✓	.04 ✓	4.11	.12	
112.20	114.90	.28 ✓	.25 ✓	6.17	.18	
114.90	116.40	.52 ✓	.61 ✓	14.05	.41	
116.40	118.00	1.63 ✓	2.10 ✓	26.40	.77	
118.00	119.50	1.58 ✓	1.80 ✓	29.14	.85	
119.50	121.00	2.93 ✓	3.84 ✓	47.31	1.38	
121.00	121.50	.27 ✓	.40 ✓	9.94	.29	
121.50	122.20	10.61 ✓	15.60 ✓	164.54	4.80	
122.20	124.00	2.85 ✓	3.54 ✓	41.48	1.21	
124.00	216.70	N/A	N/A	N/A	-	

HOLE NO: A-108 LATITUDE: 10272.31 AZIMUTH: 0.00
 HOLE LENGTH: 189.60 DEPARTURE: 7787.35 DIP: -90.00
 ELEVATION: 1270.02

DIP TESTS: DEPTH DIP AZIMUTH
 60.96 ✓ -89.00 ✓ 39.00 ✓
 121.92 ✓ -86.00 ✓ 50.00 ✓
 170.69 ✓ -86.00 ✓ 47.30 ✓

INTERVAL		ASSAYS			
FROM	TO	PB %	ZN %	AG GM/TON	AG 02/TON
0.00	69.60	N/A	N/A	N/A	
69.60	70.70	1.13 ✓	.69 ✓	20.23	.59
70.70	74.00	4.28 ✓	3.06 ✓	50.39	1.47
74.00	75.30	4.13 ✓	4.10 ✓	49.36	1.44
75.30	76.80	4.73 ✓	5.00 ✓	49.36	1.44
76.80	78.30	6.79 ✓	5.80 ✓	78.84	2.30
78.30	79.90	3.90 ✓	3.80 ✓	60.33	1.76
79.90	80.80	.28 ✓	.43 ✓	10.97	.32
80.80	82.90	.19 ✓	.20 ✓	9.94	.29
82.90	84.40	.18 ✓	.54 ✓	9.94	.29
84.40	85.90	.20 ✓	.38 ✓	7.20	.21
85.90	87.50	5.98 ✓	5.16 ✓	89.13	2.60
87.50	89.00	4.73 ✓	7.60 ✓	68.56	2.00
89.00	92.30	1.43 ✓	2.64 ✓	21.25	.62
92.30	93.00	6.54 ✓	11.41 ✓	93.93	2.74
93.00	95.10	1.75 ✓	3.18 ✓	25.37	.74
95.10	96.60	.20 ✓	.60 ✓	8.23	.24
96.60	99.70	.17 ✓	.60 ✓	4.11	.12
99.70	101.90	.12 ✓	.59 ✓	6.17	.18
101.90	104.80	1.63 ✓	3.06 ✓	26.40	.77
104.80	107.10	5.78 ✓	5.88 ✓	82.61	2.41
107.10	136.20	N/A	N/A	N/A	
136.20	138.60	1.00 ✓	1.26 ✓	20.23	.59
138.60	139.30	5.38 ✓	7.25 ✓	79.19	2.31
139.30	140.30	.18 ✓	.33 ✓	7.20	.21
140.30	140.70	3.90 ✓	5.52 ✓	72.67	2.12
140.70	143.90	2.15 ✓	1.76 ✓	32.22	.94
143.90	146.10	1.83 ✓	1.30 ✓	27.42	.80
146.10	148.40	.68 ✓	.98 ✓	12.00	.35
148.40	151.30	1.53 ✓	1.46 ✓	23.31	.68
151.30	153.00	3.00 ✓	3.00 ✓	37.37	1.09
153.00	156.10	2.00 ✓	2.46 ✓	26.40	.77
156.10	159.10	1.13 ✓	.88 ✓	16.11	.47
159.10	162.20	.12 ✓	.12 ✓	5.14	.15
162.20	163.80	.09 ✓	.06 ✓	4.11	.12
163.80	164.80	.08 ✓	.02 ✓	2.06	.06
164.80	166.20	.90 ✓	.65 ✓	20.23	.59
166.20	189.60	N/A	N/A	N/A	

HOLE NO: A-109
 HOLE LENGTH: 190.80

LATITUDE: 10701.75
 DEPARTURE: 7863.64
 ELEVATION: 1300.10

AZIMUTH: 0.00
 DIP: -90.00

DIP TESTS: DEPTH DIP AZIMUTH
 60.96 ✓ -88.00 ✓ 272.00 33.0°
 121.92 ✓ -85.00 ✓ 33.00 ✓
 182.88 ✓ -80.00 ✓ 352.00 ✓

INTERVAL		ASSAYS				
FROM	TO	PB %	ZN %	AG GM/TON	AG 02/TON	
0.00	129.10	N/A	N/A	N/A		
129.10	131.10	2.85 ✓	3.84 ✓	45.25	1.32	
131.10	132.10	2.23 ✓	4.02 ✓	35.31	1.03	
132.10	134.00	.27 ✓	.45 ✓	5.14	.15	
134.00	135.70	2.93 ✓	4.14 ✓	46.28	1.35	
135.70	137.00	6.90 ✓	10.98 ✓	92.90	2.71	
137.00	139.00	7.05 ✓	10.80 ✓	104.90	3.06	
139.00	141.00	5.33 ✓	8.10 ✓	82.61	2.41	
141.00	143.00	5.03 ✓	6.84 ✓	76.79	2.24	
143.00	145.00	3.23 ✓	4.80	57.59	1.68	
145.00	147.00	5.55 ✓	7.24	80.56	2.35	
147.00	149.00	15.02 ✓	10.10 ✓	152.20	4.44	
149.00	190.80	N/A	N/A	N/A	-	

HOLE NO: A-110 LATITUDE: 10358.85 AZIMUTH: 0.00 ✓
 HOLE LENGTH: 198.12 DEPARTURE: 7788.45 DIP: -90.00 ✓
 ELEVATION: 1273.38

DIP TESTS: DEPTH DIP AZIMUTH
 60.96 ✓ -88.00 ✓ 152.00 ✓
 121.92 ✓ -79.00 ✓ 66.00 ✓
 182.88 ✓ -74.30 ✓ 59.00 ✓

INTERVAL		ASSAYS			
FROM	TO	PB %	ZN %	AG GM/TON	AG 02/TON
0.00	41.40	N/A	N/A	N/A	-
41.40	44.00	.69 ✓	.68 ✓	10.97	.32
44.00	46.00	1.63 ✓	1.30 ✓	20.23	.59
46.00	48.00	2.85 ✓	2.88 ✓	32.22	.94
48.00	49.30	2.85 ✓	2.52 ✓	35.31	1.03
49.30	51.20	1.58 ✓	1.60 ✓	32.22	.94
51.20	58.50	N/A	N/A	N/A	-
58.50	60.50	4.05 ✓	5.90 ✓	50.39	1.47
60.50	62.50	3.60 ✓	4.86 ✓	51.42	1.50
62.50	63.50	2.93 ✓	3.54 ✓	41.48	1.21
63.50	64.80	5.04 ✓	9.73 ✓	61.36	1.79
64.80	66.00	4.73 ✓	7.04 ✓	64.45	1.88
66.00	166.70	N/A	N/A	N/A	-
166.70	167.60	1.58 ✓	2.00 ✓	26.40	.77
167.60	168.80	2.03 ✓	1.90 ✓	27.42	.80
168.80	170.90	1.00 ✓	1.20 ✓	17.14	.50
170.90	175.00	N/A	N/A	N/A	-
175.00	176.20	.12 ✓	.09 ✓	5.14	.15
176.20	198.10	N/A	N/A	N/A	-

HOLE NO: A-111 LATITUDE: 10992.84 AZIMUTH: 0.00
 HOLE LENGTH: 394.20 DEPARTURE: 7304.09 DIP: -90.00
 ELEVATION: 1326.20

DIP TESTS: DEPTH ^{-84.0°} DIP AZIMUTH
 60.96 ✓ ~~-82.00~~ 292.00 ✓
~~121.92~~ ~~-85.00~~ ✓ ~~165.00~~
 188.97 ✓ -84.00 ✓ 157.00 278.0
 243.84 ✓ -82.00 ✓ 67.00 ✓
 305.80 ✓ -80.00 ✓ 32.00 ✓
 365.76 ✓ -85.00 ✓ 92.00 ✓

INTERVAL		ASSAYS			Aq OZ/TON
FROM	TO	PB %	ZN %	AG GM/TON	
0.00	185.10	N/A	N/A	N/A	-
185.10	185.80	2.18 ✓	1.84 ✓	32.22	.94
185.80	187.60	N/A	N/A	N/A	-
187.60	190.00	1.20 ✓	1.28 ✓	16.11	.47
190.00	234.50	N/A	N/A	N/A	-
234.50	235.50	6.69 ✓	15.37 ✓	109.01	3.18
235.50	236.80	5.75 ✓	17.82 ✓	95.64	2.79
236.80	237.90	N/A	N/A	N/A	-
237.90	239.90	3.98 ✓	8.01 ✓	80.56	2.35
239.90	242.00	1.44 ✓	2.46 ✓	34.28	1.00
242.00	244.00	1.60 ✓	2.22 ✓	28.45	.83
244.00	246.00	1.08 ✓	1.76 ✓	20.23	.59
246.00	248.00	.62 ✓	.94 ✓	12.00	.35
248.00	250.00	.48 ✓	.74 ✓	8.23	.24
250.00	251.40	2.03 ✓	4.02 ✓	35.31	1.03
251.40	252.00	N/A	N/A	N/A	-
252.00	254.00	2.20 ✓	3.72 ✓	33.25	.97
254.00	256.00	2.28 ✓	3.60 ✓	36.34	1.06
256.00	258.50	2.55 ✓	4.14 ✓	35.31	1.03
258.50	271.90	N/A	N/A	N/A	-
271.90	273.90	.80 ✓	1.46 ✓	19.20	.56
273.90	275.40	.85 ✓	1.14 ✓	8.91	.26
275.40	276.20	1.03 ✓	1.72 ✓	12.00	.35
276.20	277.80	N/A	N/A	N/A	-
277.80	279.80	1.00 ✓	1.10 ✓	15.08	.44
279.80	281.00	.78	.96 ✓	14.05	.41
281.00	282.10	.88	1.12 ✓	13.03	.38
282.10	285.30	N/A	N/A	N/A	-
285.30	287.00	4.73 ✓	8.37 ✓	60.33	1.76
287.00	288.70	4.43 ✓	3.78 ✓	51.42	1.50
288.70	290.60	5.55 ✓	7.38 ✓	69.59	2.03
290.60	291.80	4.20 ✓	6.88 ✓	55.53	1.62
291.80	293.10	6.08 ✓	8.36 ✓	100.78	2.94
293.10	303.00	N/A	N/A	N/A	-
303.00	305.00	7.05 ✓	11.84 ✓	147.06	4.29
305.00	307.00	8.10	14.17 ✓	127.18	3.71
307.00	309.00	11.25 ✓	18.02 ✓	186.48	5.44
309.00	312.00	5.85	9.67 ✓	95.64	2.79
312.00	314.00	6.90 ✓	10.53 ✓	109.01	3.18
314.00	315.30	12.33 ✓	19.11 ✓	196.77	5.74
315.30	369.30	N/A	N/A	N/A	-
369.30	370.80	5.85 ✓	8.94 ✓	88.79	2.59

HOLE NO: A-112 LATITUDE: 10660.63 AZIMUTH: 0.00
 HOLE LENGTH: 172.52 DEPARTURE: 7912.97 DIP: -90.00
 ELEVATION: 1297.80

DIP TESTS:

DEPTH	DIP	AZIMUTH
85.34 ✓	-88.00 ✓	322.00 ✓
128.02 ✓	-87.00 ✓	69.00 ✓
164.59 ✓	-80.00 ✓	347.00 ✓

INTERVAL		ASSAYS				
FROM	TO	PB %	ZN %	AG GM/TON	AG G/TON	
0.00	110.40	N/A	N/A	N/A		
110.40	111.60	11.57 ✓	16.18 ✓	162.49	4.74	
111.60	113.10	9.15 ✓	10.64 ✓	136.09	3.97	
113.10	115.20	6.75 ✓	9.16 ✓	102.84	3.00	
115.20	117.70	7.05 ✓	9.17 ✓	103.87	3.03	
117.70	120.20	1.95 ✓	3.66 ✓	27.42	.80	
120.20	121.30	2.48 ✓	1.74 ✓	35.31	1.03	
121.30	121.90	5.81 ✓	5.48 ✓	84.67	2.47	
121.90	124.00	1.43 ✓	2.46 ✓	27.42	.80	
124.00	127.40	1.45 ✓	1.62 ✓	26.40	.77	
127.40	128.00	8.27 ✓	16.42 ✓	123.07	3.59	
128.00	130.80	1.43 ✓	1.80 ✓	24.34	.71	
130.80	140.90	N/A	N/A	N/A		
140.90	141.90	.98 ✓	2.52 ✓	14.05	.41	
141.90	172.50	N/A	N/A	N/A		

HOLE NO: A-113 LATITUDE: 11036.93 AZIMUTH: 0.00
 HOLE LENGTH: 474.60 DEPARTURE: 7345.95 DIP: -90.00
 ELEVATION: 1326.54

DIP TESTS:

DEPTH	DIP	AZIMUTH
60.96 ✓	-84.00 ✓	32.00 / 26.00
121.92 ✓	-81.00 ✓	112.00 ✓
182.88 ✓	-81.00 ✓	97.00 ✓
225.55 ✓	-78.00 ✓	112.00 ✓
335.28 ✓	-82.00 ✓	142.00 ✓
377.95 ✓	-80.00 ✓	97.00 / 63.0
457.20 (474.57)	-83.00 ✓	134.00 ✓

INTERVAL FROM	TO	ASSAYS			
		PB %	ZN %	AG GM/TON	AG OZ/TON
0.00	215.40	N/A	N/A	N/A	-
215.40	216.40	5.35 ✓	12.57 ✓	87.76	2.56
216.40	217.70	5.03 ✓	8.32 ✓	81.59	2.38
217.70	225.70	N/A	N/A	N/A	-
225.70	226.60	5.26 ✓	7.98 ✓	75.76	2.21
226.60	227.40	N/A	N/A	N/A	-
227.40	228.00	2.63 ✓	5.88 ✓	40.45	1.18
228.00	316.00	N/A	N/A	N/A	-
316.00	316.80	2.38 ✓	4.50 ✓	35.31	1.03
316.80	317.60	3.60 ✓	6.28 ✓	50.39	1.47
317.60	318.60	2.40 ✓	2.94 ✓	39.42	1.15
318.60	365.30	N/A	N/A	N/A	-
365.30	366.20	.50 ✓	1.22 ✓	9.94	.29
366.20	367.20	2.15 ✓	4.20 ✓	36.34	1.06
367.20	368.20	5.40 ✓	8.71 ✓	86.73	2.53
368.20	369.20	3.45 ✓	6.12 ✓	59.30	1.73
369.20	370.20	4.73 ✓	8.10 ✓	82.61	2.41
370.20	370.80	6.08 ✓	9.73 ✓	111.07	3.24
370.80	371.80	.73 ✓	1.34 ✓	8.91	.26
371.80	372.80	1.63 ✓	2.52 ✓	22.28	.65
372.80	373.50	.83 ✓	1.58 ✓	12.00	.35
373.50	374.50	5.83 ✓	6.89 ✓	84.67	2.47
374.50	375.50	6.15 ✓	10.35 ✓	96.67	2.82
375.50	376.70	2.85 ✓	5.64 ✓	41.48	1.21
376.70	377.50	4.58 ✓	8.09 ✓	78.84	2.30
377.50	377.90	.96 ✓	.66 ✓	15.08	.44
377.90	378.90	2.13 ✓	3.30 ✓	42.51	1.24
378.90	379.80	2.70 ✓	3.30 ✓	39.42	1.15
379.80	380.20	.85 ✓	.86 ✓	13.03	.38
380.20	474.60	N/A	N/A	N/A	-

SPECIFIC TO MOORE BUSINESS FORMS 4

HOLE NO: A-114 LATITUDE: 10259.84 AZIMUTH: 0.00
 HOLE LENGTH: 221.60 DEPARTURE: 7715.81 DIP: -90.00
 ELEVATION: 1269.77

DIP TESTS: DEPTH DIP AZIMUTH
 60.96 ✓ -90.00 ✓ 0.00 ✓
 109.73 ✓ -85.00 ✓ 54.00 ✓
 170.69 ✓ -83.00 ✓ 40.00 ✓
 219.45 ✓ -80.00 ✓ 13.00 ✓

propari

INTERVAL		ASSAYS				AG
FROM	TO	PB	ZN	AG		AG
		%	%	GM/TON		02/TON
0.00	93.20	N/A	N/A	N/A		-
93.20	95.20	.68 ✓	.30 ✓	18.17		.53
95.20	97.70	1.20 ✓	.94 ✓	19.20		.56
97.70	98.70	N/A	N/A	N/A		-
98.70	100.70	1.43 ✓	1.16 ✓	24.34		.71
100.70	102.70	1.45 ✓	1.56 ✓	24.34		.71
102.70	104.70	1.15 ✓	.30 ✓	20.23		.59
104.70	106.70	.98 ✓	.43 ✓	27.42		.80
106.70	108.50	1.15 ✓	.95 ✓	20.23		.59
108.50	112.60	N/A	N/A	N/A		-
112.60	114.60	1.58 ✓	1.36 ✓	25.37		.74
114.60	116.60	1.23 ✓	.98 ✓	18.17		.53
116.60	118.60	1.02 ✓	.77 ✓	19.20		.56
118.60	120.60	1.75 ✓	1.40 ✓	25.37		.74
120.60	122.60	1.63 ✓	1.12 ✓	25.37		.74
122.60	124.60	1.63 ✓	1.34 ✓	24.34		.71
124.60	127.00	N/A	N/A	N/A		-
127.00	129.00	1.04 ✓	.68 ✓	23.31		.68
129.00	131.00	1.24 ✓	.80 ✓	24.34		.71
131.00	133.00	1.18 ✓	.66 ✓	24.34		.71
133.00	135.00	2.30 ✓	2.34 ✓	42.51		1.24
135.00	137.00	3.08 ✓	3.36 ✓	43.54		1.27
137.00	137.90	.74 ✓	.82 ✓	9.94		.29
137.90	138.80	N/A	N/A	N/A		-
138.80	140.50	1.30 ✓	1.12 ✓	19.20		.56
140.50	141.90	4.05 ✓	4.14 ✓	40.45		1.18
141.90	143.90	.80 ✓	1.30 ✓	18.17		.53
143.90	145.40	.15 ✓	.25 ✓	8.91		.26
145.40	147.40	2.08 ✓	2.46 ✓	35.31		1.03
147.40	149.70	1.10 ✓	.66 ✓	22.28		.65
149.70	221.60	N/A	N/A	N/A		-

←

HOLE NO: A-115 LATITUDE: 10948.14 AZIMUTH: 0.00
 HOLE LENGTH: 448.10 DEPARTURE: 7260.70 DIP: -90.00
 ELEVATION: 1326.86

DIP TESTS:	DEPTH	DIP	AZIMUTH
	60.96✓	-85.30✓	50.20✓
	182.88✓	-84.00✓	87.20✓
	243.84✓	-82.00✓	103.20✓
	304.80✓	-79.00✓	102.20✓
	365.76✓	-79.00✓	97.20✓

INTERVAL		ASSAYS				AG	
FROM	TO	PB %	ZN %	AG GM/TON	AG O2/TON		
0.00	221.20	N/A	N/A	N/A	-		
221.20	222.20	2.08✓	1.50✓	34.28	1.00		
222.20	224.00	.95✓	.58✓	16.11	.47		
224.00	225.80	3.90✓	4.38✓	56.56	1.65		
225.80	325.90	N/A	N/A	N/A	-		
325.90	327.40	.23✓	.30✓	4.11	.12		
327.40	329.00	1.63✓	1.34✓	22.28	.65		
329.00	330.90	.63✓	.42✓	9.94	.29		
330.90	331.90	1.35✓	.82✓	22.28	.65		
331.90	332.65	.33✓	.88	9.94	.29		.38
332.65	333.45	4.35✓	5.04✓	68.56	2.00		
333.45	334.50	.93✓	1.08✓	19.20	.56		
334.50	336.20	.33✓	.40✓	9.94	.29		
336.20	337.70	1.48✓	1.98✓	23.31	.68		
337.70	339.20	.55✓	.30✓	10.97	.32		
339.20	340.70	.08✓	.18✓	2.06	.06		
340.70	342.00	.18✓	.18✓	4.11	.12		
342.00	343.40	.43✓	.24✓	8.23	.24		
343.40	344.70	.25✓	.10✓	8.23	.24		
344.70	346.00	.20✓	.06✓	5.14	.15		
346.00	347.50	.43✓	.26✓	7.20	.21		
347.50	349.00	.35✓	.24✓	8.23	.24		
349.00	349.80	.60✓	.46✓	9.94	.29		
349.80	350.50	4.13✓	4.26✓	60.33	1.76		
350.50	351.80	.48✓	.92✓	13.03	.38		
351.80	353.30	.20✓	.16✓	2.06	.06		
353.30	354.80	.45✓	.50✓	8.91	.26		
354.80	356.20	4.28✓	5.52✓	50.39	1.47		
356.20	357.90	1.60✓	2.76✓	22.28	.65		
357.90	360.50	N/A	N/A	N/A	-		
360.50	361.30	2.23✓	4.68✓	32.22	.94		
361.30	408.40	N/A	N/A	N/A	-		
408.40	410.20	1.40✓	2.34✓	20.23	.59		
410.20	412.50	N/A	N/A	N/A	-		
412.50	413.40	3.38✓	.52✓	30.17	.88		
413.40	419.90	N/A	N/A	N/A	-		
419.90	420.90	3.23✓	4.50✓	35.31	1.03		
420.90	421.90	1.75✓	1.90✓	30.17	.88		
421.90	422.80	5.78✓	8.31✓	63.42	1.85		
422.80	423.80	5.48✓	7.07✓	62.39	1.82		
423.80	424.80	3.68✓	6.94✓	34.28	1.00		
424.80	425.80	3.23✓	5.28✓	42.51	1.24		
425.80	426.80	.25✓	2.46	5.14	.15		.26

HOLE NO: A-116 LATITUDE: 10746.22 AZIMUTH: 0.00
 HOLE LENGTH: 181.70 DEPARTURE: 7905.17 DIP: -90.00
 ELEVATION: 1304.60

DIP TESTS: DEPTH DIP AZIMUTH
 73.15 ✓ -88.00 ✓ 57.00 ✓
 146.30 ✓ -78.00 ✓ 52.00 ✓

INTERVAL		ASSAYS			
FROM	TO	PB %	ZN %	AG GM/TON	
0.00	110.90	N/A	N/A	N/A	AG 02/TON
110.90	111.90	1.63 ✓	2.94 ✓	27.42	.80
111.90	114.20	1.63 ✓	2.82 ✓	22.28	.65
114.20	181.70	N/A	N/A	N/A	-

HOLE NO: A-117 LATITUDE: 10524.96 AZIMUTH: 0.00
 HOLE LENGTH: 214.27 DEPARTURE: 7700.87 DIP: -90.00
 ELEVATION: 1286.46

DIP TESTS: DEPTH DIP AZIMUTH
 60.96 ✓ -83.00 ✓ 47.00 ✓
 121.92 ✓ -82.00 ✓ 42.00 ✓
 161.54 ✓ -86.00 ✓ 37.00 ✓
 -80.2

INTERVAL		ASSAYS				
FROM	TO	PB %	ZN %	AG GM/TON	Ag OZ/TON	
0.00	80.80	N/A	N/A	N/A	-	
80.80	81.20	6.08 ✓	11.95 ✓	97.70	2.85	
81.20	81.70	14.62 ✓	25.08 ✓	239.96	7.00	
81.70	82.30	10.27 ✓	13.77 ✓	161.46	4.71	
82.30	83.30	13.13 ✓	24.65 ✓	233.79	6.82	
83.30	83.90	11.21 ✓	23.13 ✓	202.59	5.91	
83.90	85.20	8.22 ✓	18.67 ✓	164.54	4.80	
85.20	86.00	11.65 ✓	23.40 ✓	211.85	6.18	
86.00	87.00	7.65 ✓	11.52 ✓	113.12	3.30	
87.00	88.00	4.43 ✓	5.76 ✓	60.33	1.76	
88.00	89.00	5.85 ✓	13.68 ✓	92.90	2.71	
89.00	89.60	6.39 ✓	9.89 ✓	104.90	3.06	
89.60	97.10	N/A	N/A	N/A	-	
97.10	98.10	5.33 ✓	8.89 ✓	99.75	2.91	8.88
98.10	99.30	N/A	N/A	N/A	-	
99.30	100.30	5.88 ✓	8.82 ✓	100.78	2.94	
100.30	101.30	3.90 ✓	6.77 ✓	58.62	1.71	
101.30	102.30	5.63 ✓	8.15 ✓	110.04	3.21	
102.30	103.30	5.03 ✓	6.48 ✓	83.64	2.44	
103.30	150.30	N/A	N/A	N/A	-	
150.30	151.10	5.78 ✓	5.40 ✓	81.59	2.38	
151.10	151.40	N/A	N/A	N/A	-	
151.40	152.40	6.05 ✓	10.21 ✓	84.67	2.47	
152.40	153.40	.70 ✓	1.42 ✓	23.31	.68	
153.40	154.40	1.28 ✓	1.50 ✓	38.39	1.12	
154.40	155.10	1.50 ✓	1.30 ✓	27.42	.80	
155.10	156.10	3.68 ✓	3.30 ✓	48.33	1.41	
156.10	157.90	9.21 ✓	12.52 ✓	122.04	3.56	
157.90	212.30	N/A	N/A	N/A	-	

SPECIAL TO MOORE BUSINESS FORMS 4

HOLE NO: A-118 LATITUDE: 11076.78 AZIMUTH: 0.00
 HOLE LENGTH: 468.50 DEPARTURE: 7388.58 DIP: -90.00
 ELEVATION: 1325.26

DIP TESTS:	DEPTH	DIP	AZIMUTH
	✓60.96	-80.00 ✓	123.00 ✓
	✓182.88 ✓	-78.00 ✓	121.00 ✓
	243.84 ✓	-78.00 ✓	132.00 ✓
	335.28 ✓	-78.00 ✓	142.00 ✓
	396.24 ✓	-78.00 ✓	142.00 ✓
	426.72 ✓	-77.00 ✓	142.00 ✓

INTERVAL		ASSAYS				
FROM	TO	PB %	ZN %	AG GM/TON	AG 021/TON	
0.00	162.00	N/A	N/A	N/A	-	
162.00	164.00	2.43 ✓	3.48 ✓	37.37	1.09	
164.00	164.40	N/A	N/A	N/A	-	
164.40	165.00	1.78 ✓	2.52 ✓	30.17	.88	
165.00	203.00	N/A	N/A	N/A	-	
203.00	204.00	1.75 ✓	3.06 ✓	30.17	.88	
204.00	205.00	3.23 ✓	4.92 ✓	37.37	1.09	
205.00	206.00	2.85 ✓	4.80 ✓	34.28	1.00	
206.00	207.00	1.70 ✓	2.10 ✓	20.23	.59	
207.00	208.00	1.65 ✓	4.20 ✓	21.25	.62	
208.00	209.00	2.70 ✓	3.30 ✓	30.17	.88	
209.00	210.00	2.28 ✓	2.52 ✓	28.45	.83	
210.00	211.00	1.68 ✓	1.94 ✓	20.23	.59	
211.00	212.00	1.70 ✓	1.08 ✓	23.31	.68	
212.00	213.00	.93 ✓	.86 ✓	10.97	.32	
213.00	214.00	.63 ✓	.68 ✓	9.94	.29	
214.00	215.00	2.10 ✓	.94 ✓	29.14	.85	
215.00	216.90	.30 ✓	.32 ✓	8.23	.24	
216.90	217.50	5.33 ✓	6.93 ✓	75.76	2.21	
217.50	218.50	3.98 ✓	6.60 ✓	57.59	1.68	
218.50	220.00	1.65 ✓	4.14 ✓	27.42	.80	
220.00	226.00	N/A	N/A	N/A	-	
226.00	226.80	3.68 ✓	4.33 ✓	52.45	1.53	
226.80	227.80	.58 ✓	.58 ✓	9.94	.29	
227.80	228.80	3.75 ✓	2.88 ✓	47.31	1.38	
228.80	229.80	5.39 ✓	4.92 ✓	75.76	2.21	
229.80	230.30	1.48 ✓	1.98 ✓	26.40	.77	
230.30	231.30	6.16 ✓	10.58 ✓	97.70	2.85	
231.30	232.30	7.11 ✓	10.86 ✓	100.78	2.94	
232.30	233.30	5.57 ✓	10.76 ✓	90.84	2.65	
233.30	234.30	3.98 ✓	7.52 ✓	60.33	1.76	
234.30	235.30	1.83 ✓	3.72 ✓	27.42	.80	
235.30	240.50	N/A	N/A	N/A	-	
240.50	241.70	1.48 ✓	1.90 ✓	24.34	.71	
241.70	243.40	2.18 ✓	3.96 ✓	34.28	1.00	
243.40	245.40	.73 ✓	.94 ✓	20.23	.59	
245.40	247.40	.63 ✓	.84 ✓	23.31	.68	
247.40	248.70	.88 ✓	1.30 ✓	19.20	.56	
248.70	251.50	N/A	N/A	N/A	-	
251.50	252.10	1.43 ✓	2.64 ✓	25.37	.74	
252.10	290.20	N/A	N/A	N/A	-	
290.20	290.50	5.76 ✓	10.07 ✓	85.70	2.56	

SHEET NO MOORE BUSINESS FORMS 4

HOLE NO: A-118

INTERVAL		ASSAYS			
FROM	TO	PB %	ZN %	AG GM/TON	AG OZ/TON
290.50	291.50	5.75✓	3.00✓	68.56	2.00
291.50	292.50	3.00✓	4.00✓	44.22	1.29
292.50	355.50	N/A	N/A	N/A	-
355.50	356.50	.73✓	.80✓	13.03	.38
356.50	357.20	3.60✓	3.90✓	55.53	1.62
357.20	358.90	2.28✓	2.46✓	35.31	1.03
358.90	359.70	2.03✓	4.26✓	25.37	.74
359.70	360.60	1.88✓	3.30✓	28.45	.83
360.60	369.40	N/A	N/A	N/A	-
369.40	370.90	5.03	7.63	84.67	2.47
370.90	372.80	N/A	N/A	N/A	-
372.80	374.30	3.90✓	4.68✓	54.51	1.59
374.30	375.70	.15✓	.26✓	13.03	.38
375.70	377.00	1.38✓	2.52✓	28.45	.83
377.00	377.60	5.70✓	8.83✓	74.73	2.18
377.60	379.20	2.38✓	2.34✓	41.48	1.21
379.20	380.70	3.68✓	5.82✓	54.51	1.59
380.70	381.90	4.43✓	8.38✓	70.62	2.06
381.90	417.70	N/A	N/A	N/A	-
417.70	418.80	4.35✓	4.98✓	57.59	1.68
418.80	420.60	N/A	N/A	N/A	-
420.60	421.60	1.35✓	1.92✓	21.25	.62
421.60	422.60	1.78✓	1.26✓	28.45	.83
422.60	423.60	1.83✓	2.10✓	28.45 14.05	.41
423.60	424.60	.83✓	.40✓	14.05 9.94	.29
424.60	427.60	.70✓	.60✓	9.94 130.94	3.82
427.60	468.50	N/A	N/A	N/A	-

SPEED TO MOORE BUSINESS FORMS 4

HOLE NO: A-119 LATITUDE: 10445.49 AZIMUTH: 0.00
 HOLE LENGTH: 172.82 DEPARTURE: 7871.16 DIP: -90.00
 ELEVATION: 1284.22

DIP TESTS:	DEPTH	DIP	AZIMUTH
	60.96 ✓	-85.00 ✓	72.00 ✓
	115.82 ✓	-78.00 ✓	63.00 ✓
	158.50 ✓	-75.00 ✓	62.00 ✓

INTERVAL		ASSAYS			
FROM	TO	PB %	ZN %	AG GM/TON	AG OZ/TON
0.00	49.00	N/A	N/A	N/A	—
49.00	51.20	2.43 ✓	6.56 ✓	43.54	1.27
51.20	52.30	1.78 ✓	4.98 ✓	37.37	1.09
52.30	52.90	3.83 ✓	7.41 ✓	55.53	1.62
52.90	172.80	N/A	N/A	N/A	—

HOLE NO: A-120 LATITUDE: 11118.58 AZIMUTH: 0.00
 HOLE LENGTH: 453.24 DEPARTURE: 7427.24 DIP: -90.00
 ELEVATION: 1324.73

DIP TESTS:	DEPTH	DIP	AZIMUTH
	60.96✓	-84.00✓	97.00 127.0
	121.92✓	-83.00✓	97.00 131.0
	182.88✓	-84.00✓	120.00 120 153.0
	243.84✓	-82.00✓	115.00 148.0
	304.80✓	-78.00✓	105.00 138.0
	453.24	-78.00✓	110.00 143.0
	365.76		

INTERVAL	ASSAYS	AG
FROM TO	PB % ZN % AG GM/TON	g 2/TON
0.00 109.10	N/A N/A N/A	-
109.10 111.10	3.08✓ 4.80✓ 39.42	1.15
111.10 113.90	2.48✓ 4.38✓ 37.37	1.09
113.90 115.10	4.73✓ 8.42✓ 68.56	2.00
115.10 116.80	N/A N/A N/A	-
116.80 119.20	3.08✓ 5.04✓ 46.28	1.35
119.20 120.70	N/A N/A N/A	-
120.70 122.80	1.53✓ 3.12✓ 22.28	.65
122.80 124.00	4.35✓ 7.06✓ 59.30	1.73
124.00 125.00	2.93✓ 4.08✓ 35.31	1.03
125.00 126.20	.70✓ 1.26✓ 12.00	.35
126.20 127.10	.48✓ .82✓ 9.94	.29
127.10 128.30	.43✓ 1.02✓ 8.23	.24
128.30 130.40	1.28✓ .82✓ 20.23	.59
130.40 134.80	N/A N/A N/A	-
134.80 136.20	1.53✓ 2.94✓ 21.25	.62
136.20 137.70	2.25✓ 1.98✓ 26.40	.77
137.70 139.60	2.48✓ 3.66✓ 23.31	.68
139.60 140.80	3.38✓ 6.51✓ 45.25	1.32
140.80 142.30	2.48✓ 4.50✓ 50.39	1.47
142.30 143.80	3.30✓ 6.78✓ 33.25	.97
143.80 145.60	4.35✓ 6.73✓ 50.39	1.47
145.60 146.70	N/A N/A N/A	-
146.70 147.40	3.00✓ 5.10✓ 47.31	1.38
147.40 151.70	N/A N/A N/A	-
151.70 153.20	2.78✓ 5.11✓ 35.31	1.03
153.20 154.50	3.45✓ 5.04✓ 42.51	1.24
154.50 156.40	1.93✓ 3.90✓ 28.45	.83
156.40 162.20	N/A N/A N/A	-
162.20 164.20	1.78✓ 3.90✓ 26.40	.77
164.20 165.30	N/A N/A N/A	-
165.30 166.70	1.50✓ 2.10✓ 25.37	.74
166.70 168.80	1.30✓ 1.98✓ 27.42	.80
168.80 170.00	1.78✓ 2.28✓ 26.40	.77
170.00 172.00	2.28✓ 3.72✓ 35.31	1.03
172.00 174.00	2.40✓ 3.90✓ 41.48	1.21
174.00 176.00	1.88✓ 3.72✓ 29.14	.85
176.00 178.00	2.25✓ 6.48✓ 38.39	1.12
178.00 180.00	1.13✓ 2.64✓ 20.23	.59
180.00 180.70	2.93✓ 3.66✓ 53.48	1.56
180.70 183.30	N/A N/A N/A	-
183.30 184.40	3.98✓ 6.00✓ 49.36	1.44

SPECIAL TO MOORE BUSINESS FORMS

HOLE NO: A-120

INTERVAL		ASSAYS				
FROM	TO	PB %	ZN %	AG GM/TON	AG OZ/TON	
184.40	185.80	.10 ✓	.12 ✓	3.09	.09	
185.80	187.00	3.30 ✓	7.36 ✓	61.36	1.79	
187.00	189.30	.38	.34	5.14	.15	
189.30	190.50	3.75 ✓	6.00 ✓	63.42	1.85	
190.50	192.10	4.88 ✓	5.48 ✓	70.62	2.06	
192.10	193.20	.08 ✓	.14 ✓	3.09	.09	
193.20	194.50	3.15 ✓	6.33 ✓	55.53	1.62	
194.50	220.80	N/A	N/A	N/A	-	
220.80	222.80	4.88 ✓	7.34 ✓	91.87	2.68	
222.80	224.30	4.43 ✓	7.18 ✓	74.73	2.18	
224.30	225.80	.88 ✓	1.98 ✓	15.08	.44	
225.80	228.10	.53 ✓	1.68 ✓	10.97	.32	
228.10	307.00	N/A	N/A	N/A	-	
307.00	307.80	7.02 ✓	14.93 ✓	126.15	3.68	
307.80	309.60	5.70 ✓	11.26 ✓	102.84	3.00	
309.60	311.80	.93 ✓	1.88 ✓	24.34	.71	
311.80	313.30	5.74 ✓	9.45 ✓	81.59	2.38	
313.30	314.00	N/A	N/A	N/A	-	
314.00	317.30	4.88 ✓	5.76 ✓	65.47	1.91	
317.30	318.80	N/A	N/A	N/A	-	
318.80	319.70	5.33 ✓	6.34 ✓	91.87	2.68	
319.70	321.70	N/A	N/A	N/A	-	
321.70	322.80	4.35 ✓	8.15 ✓	75.76	2.21	
322.80	324.80	4.43 ✓	5.88 ✓	71.65	2.09	
324.80	326.80	3.90 ✓	5.64 ✓	67.53	1.97	
326.80	327.80	4.43 ✓	6.44 ✓	80.56	2.35	
327.80	335.00	N/A	N/A	N/A	-	
335.00	335.40	4.50 ✓	6.79 ✓	97.70	2.85	
335.40	371.50	N/A	N/A	N/A	-	
371.50	373.80	.33 ✓	.56 ✓	7.20	.21	
373.80	375.20	.15 ✓	.16 ✓	4.11	.12	
375.20	379.20	N/A	N/A	N/A	-	
379.20	380.70	.03 ✓	.06 ✓	4.11	.12	
380.70	381.40	1.98 ✓	4.14 ✓	39.42	1.15	
381.40	382.10	8.67 ✓	17.65 ✓	125.12	3.65	
382.10	388.00	N/A	N/A	N/A	-	
388.00	390.40	.88 ✓	1.10 ✓	18.17	.53	
390.40	391.30	.06 ✓	.06 ✓	2.06	.06	
391.30	393.90	2.93 ✓	4.26 ✓	44.22	1.29	
393.90	403.80	N/A	N/A	N/A	-	
403.80	405.10	4.95 ✓	7.41 ✓	62.73	1.83	
405.10	407.40	1.30 ✓	1.12 ✓	25.37	.74	
407.40	408.60	5.18 ✓	6.83 ✓	65.47	1.91	
408.60	453.20	N/A	N/A	N/A	-	

SHEET 10 MOORE BUSINESS FORMS 4

HOLE NO: A-121
 HOLE LENGTH: 260.00

LATITUDE: 10618.20
 DEPARTURE: 7780.26
 ELEVATION: 1293.13

AZIMUTH: 0.00
 DIP: -90.00

DIP TESTS:	DEPTH	DIP	AZIMUTH
	60.96 ✓	-86.00 ✓	94.00 ✓
134.11	121.92	-83.00 ✓	83.00 ✓
	207.26 ✓	-80.00 ✓	89.00 ✓
	249.94 ✓	-77.00 ✓	97.00 ✓

INTERVAL		ASSAYS			AG	
FROM	TO	PB %	ZN %	AG GM/TON	AG	
0.00	156.80	N/A	N/A	N/A	02/70W	-
156.80	157.90	3.60 ✓	3.90 ✓	65.47	1.91	
157.90	158.40	3.06	6.44 ✓	47.31	1.38	3.00
158.40	159.10	N/A	N/A	N/A	-	
159.10	160.30	.58 ✓	1.06 ✓	9.94	.29	
160.30	180.40	N/A	N/A	N/A	-	
180.40	181.20	7.50 ✓	8.53 ✓	98.73	2.88	
181.20	182.80	.80 ✓	.48 ✓	15.08	.44	
182.80	185.10	1.28 ✓	.94 ✓	18.17	.53	
185.10	186.40	1.10 ✓	.94 ✓	15.08	.44	
186.40	188.40	.88 ✓	.80 ✓	15.08	.44	
188.40	189.90	3.90 ✓	6.11 ✓	60.33	1.76	
189.90	192.60	1.45 ✓	1.40 ✓	19.20	.56	
192.60	193.80	2.70 ✓	1.22 ✓	25.37	.74	
193.80	194.80	.80 ✓	.38 ✓	8.91	.26	
194.80	197.00	.75 ✓	1.02 ✓	7.20	.21	
197.00	198.70	.85 ✓	1.22 ✓	9.94	.29	
198.70	199.90	.48 ✓	1.04 ✓	8.91	.26	
199.90	201.50	1.60 ✓	1.18 ✓	23.65	.69	
201.50	202.80	5.53 ✓	6.33 ✓	74.73	2.18	
202.80	203.60	2.93 ✓	3.54 ✓	37.37	1.09	
203.60	204.20	.65 ✓	.54 ✓	12.00	.35	
204.20	206.00	1.83 ✓	1.60 ✓	21.25	.62	
206.00	208.20	1.63 ✓	1.48 ✓	28.45	.83	
208.20	209.10	3.23 ✓	4.74 ✓	51.42	1.50	
209.10	210.00	.10 ✓	.10 ✓	2.06	.06	
210.00	260.00	N/A	N/A	N/A	-	

0.00 - 59.4	N/A	N/A	N/A	-
59.4 - 62.8	10.58	17.97	130.95	3.82
62.8 - 64.8	8.01	12.97	129.92	3.79
64.8 - 65.8	.63	1.32	13.03	.38
65.8 - 156.8	N/A	N/A	N/A	-

SPEECH TO MOORE BUSINESS FORMS 4

HOLE NO: A-122 LATITUDE: 10443.29 AZIMUTH: 0.00
 HOLE LENGTH: 232.60 DEPARTURE: 7784.10 DIP: -90.00
 ELEVATION: 1280.78

DIP TESTS:	DEPTH	DIP	AZIMUTH
	60.96 ✓	-86.00 ✓	94.00 ✓
	91.44 ✓	-85.00 ✓	87.00 ✓
	152.40 ✓	-84.00 ✓	80.00 ✓
	228.60 ✓	-77.00 ✓	72.00 ✓

INTERVAL		ASSAYS			
FROM	TO	PB	ZN	AG	AG
		%	%	GM/TON	OZ/TON
0.00	120.60	N/A	N/A	N/A	-
120.60	121.30	1.48 ✓	1.14 ✓	30.17	.88
121.30	123.10	5.63 ✓	8.65 ✓	100.78	2.94
123.10	137.00	N/A	N/A	N/A	-
137.00	138.00	.33 ✓	.54 ✓	8.23	.24
138.00	139.70	.95 ✓	1.28 ✓	16.11	.47
139.70	140.90	.88 ✓	.74 ✓	21.25	.62
140.90	202.20	N/A	N/A	N/A	-
202.20	203.00	4.95 ✓	5.53 ✓	72.67	2.12
203.00	204.10	1.20 ✓	1.06 ✓	19.20	.56
204.10	206.70	4.05 ✓	3.00 ✓	49.36	1.44
206.70	209.10	2.50 ✓	1.74 ✓	40.45	1.18
209.10	209.70	.48 ✓	.38 ✓	10.97	.32
209.70	211.00	3.68 ✓	2.46 ✓	42.51	1.24
211.00	213.70	N/A	N/A	N/A	-
213.70	214.10	.65 ✓	.24 ✓	9.94	.29
214.10	215.60	3.19 ✓	2.52 ✓	40.45	1.18
215.60	216.40	.63 ✓	.34 ✓	15.08	.44
216.40	219.00	3.68 ✓	3.00 ✓	45.25	1.32
219.00	220.80	1.65 ✓	.92 ✓	24.34	.71
220.80	221.60	N/A	N/A	N/A	-
221.60	222.70	2.70 ✓	5.40 ✓	38.39	1.12
222.70	232.60	N/A	N/A	N/A	-

DIAMOND DRILL LOG MA

STER FILE

HOLE NO: A-123
HOLE LENGTH: 464.82

LATITUDE: 11120.20
DEPARTURE: 7345.44
ELEVATION: 1328.52

AZIMUTH: 0.00
DIP: -90.00

DIP TESTS:	DEPTH	DIP	AZIMUTH
	30.48 ✓	-82.00 ✓	116.00 ✓
	91.44 ✓	-81.00 ✓	107.00 ✓
/52.40	170.69 ✓	-83.00 ✓	127.00 ✓
	213.36 ✓	-82.00 ✓	101.00 ✓
	274.32 ✓	-83.00 ✓	106.00 ✓
	377.95 ✓	-75.00 ✓	144.00 ✓

INTERVAL		ASSAYS			AG
FROM	TO	PB %	ZN %	AG GM/TON	AG OZ/TON
0.00	113.20	N/A	N/A	N/A	
113.20	115.00	2.38 ✓	3.48 ✓	37.37	1.09
115.00	116.00	1.83 ✓	2.00 ✓	24.34	.71
116.00	118.00	1.93 ✓	3.54 ✓	26.40	.77
118.00	120.00	1.90 ✓	3.48 ✓	29.14	.85
120.00	122.00	1.75 ✓	3.18 ✓	26.40	.77
122.00	124.00	1.99 ✓	3.00 ✓	28.45	.83
124.00	127.60	N/A	N/A	N/A	
127.60	128.90	1.84 ✓	2.76 ✓	29.14	.85
128.90	130.00	1.48 ✓	2.46 ✓	24.34	.71
130.00	132.60	N/A	N/A	N/A	
132.60	134.40	1.23 ✓	1.66 ✓	28.45	.83
134.40	135.90	2.50 ✓	4.02 ✓	36.34	1.06
135.90	136.80	2.48 ✓	5.40 ✓	35.31	1.03
136.80	137.80	1.78 ✓	2.76 ✓	28.45	.83
137.80	139.30	1.93 ✓	2.46 ✓	30.17	.88
139.30	141.40	2.45 ✓	3.18 ✓	37.37	1.09
141.40	142.30	2.59 ✓	3.90 ✓	41.48	1.21
142.30	144.50	2.70 ✓	4.02 ✓	43.54	1.27
144.50	145.40	3.53 ✓	5.93 ✓	65.47	1.91
145.40	146.60	2.78 ✓	4.02 ✓	46.28	1.35
146.60	150.60	N/A	N/A	N/A	
150.60	151.50	1.23 ✓	1.18 ✓	21.25	.62
151.50	156.50	N/A	N/A	N/A	
156.50	158.50	2.50 ✓	4.38 ✓	40.45	1.18
158.50	160.00	2.78 ✓	4.20 ✓	44.22	1.29
160.00	160.70	1.73 ✓	2.64 ✓	29.14	.85
160.70	175.60	N/A	N/A	N/A	
175.60	177.10	.58 ✓	.68 ✓	9.94	
177.10	178.60	.43 ✓	.70 ✓	8.91	
178.60	188.50	N/A	N/A	N/A	
188.50	189.40	1.53 ✓	3.48 ✓	19.20	
189.40	191.10	2.18 ✓	5.40 ✓	31.19	
191.10	191.60	N/A	N/A	N/A	
191.60	193.50	2.93 ✓	5.64 ✓	33.25	
193.50	194.50	3.23 ✓	7.20 ✓	50.39	
194.50	195.70	3.75 ✓	8.00 ✓	63.42	
195.70	196.30	4.58 ✓	4.02 ✓	59.30	
196.30	197.60	2.85 ✓	2.40 ✓	33.25	
197.60	200.10	1.93 ✓	2.14 ✓	28.45	
200.10	201.50	2.48 ✓	5.76 ✓	46.28	
201.50	203.30	1.88 ✓	4.68 ✓	34.28	

SPECIFIC MOORE BUSINESS FORMS 4

HOLE NO: A-123

INTERVAL		ASSAYS				
FROM	TO	PB %	ZN %	AG GM/TON	AG OZ/TON	
203.30	204.20	1.70✓	4.08✓	26.40	.77	
204.20	205.50	2.18✓	1.47✓	25.37	.74	
205.50	209.40	N/A	N/A	N/A	-	
209.40	211.20	3.60✓	3.60✓	38.39	1.12	
211.20	229.60	N/A	N/A	N/A	-	
229.60	230.70	2.85✓	6.29✓	48.33	1.41	
230.70	230.80	N/A	N/A	N/A	-	
230.80	231.90	2.63✓	4.50✓	36.34	1.06	
231.90	233.50	1.23✓	1.40✓	18.17	.53	
233.50	234.20	5.71✓	7.18✓	88.79	2.59	
234.20	234.60	N/A	N/A	N/A	-	
234.60	236.10	1.18✓	1.70✓	19.20	.56	
236.10	237.60	.58✓	.76✓	7.20	.21	
237.60	239.10	N/A	N/A	N/A	-	
239.10	239.90	2.38✓	2.14✓	33.25	.97	
239.90	244.00	N/A	N/A	N/A	-	
244.00	246.00	4.65✓	6.90✓	68.56	2.00	
246.00	248.00	4.73✓	8.11✓	77.82	2.27	
248.00	250.00	4.20✓	8.07✓	64.45	1.88	
250.00	251.80	.75✓	1.54✓	12.00	.35	
251.80	253.00	7.73✓	16.75✓	143.29	4.18	
253.00	254.00	2.70✓	4.02✓	46.28	1.35	
254.00	273.10	N/A	N/A	N/A	-	
273.10	274.60	5.21✓	11.86✓	84.67	2.47	
274.60	275.70	6.93✓	14.44✓	123.07	3.59	
275.70	278.00	N/A	N/A	N/A	-	
278.00	279.30	2.43✓	5.64✓	38.39	1.12	
279.30	281.00	5.11✓	6.05✓	76.79	2.24	
281.00	282.50	3.75✓	5.86✓	58.62	1.71	
282.50	284.00	4.35✓	5.64✓	73.70	2.15	
284.00	285.60	4.95✓	7.58✓	85.70	2.50	
285.60	286.70	3.68✓	7.69✓	68.56	2.00	
286.70	299.10	N/A	N/A	N/A	-	
299.10	300.40	2.63✓	3.42✓	44.22	1.29	
300.40	302.00	1.15✓	2.10✓	18.17	.53	
302.00	304.00	1.88✓	2.76✓	30.17	.88	
304.00	306.00	3.15✓	4.92✓	50.39	1.47	
306.00	307.20	3.98✓	6.23✓	60.33	1.76	
307.20	316.30	N/A	N/A	N/A	-	
316.30	317.80	.40✓	1.36✓	5.14	.15	
317.80	319.40	.38✓	.95✓	4.11	.12	
319.40	320.60	N/A	N/A	N/A	-	
320.60	322.60	.50✓	.92✓	8.91	.26	
322.60	324.50	.23✓	.52✓	5.14	.15	
324.50	374.00	N/A	N/A	N/A	-	
374.00	375.20	1.68✓	1.92✓	25.37	.74	
375.20	376.40	7.65✓	11.53✓	126.15	3.68	
376.40	377.40	4.95✓	5.76✓	68.56	2.00	
377.40	378.90	N/A	N/A	N/A	-	
378.90	380.20	3.83✓	2.10✓	50.39	1.47	
380.20	383.40	N/A	N/A	N/A	-	
383.40	384.10	7.41✓	3.18✓	106.95	3.12	

SPECIAL MOORE BUSINESS FORMS 4

HOLE NO: A-123

INTERVAL		ASSAYS			
FROM	TO	PB %	ZN %	AG GM/TON	AG OZ/TON
384.10	384.80	N/A	N/A	N/A	-
384.80	385.60	2.48 ✓	3.48 ✓	42.51	1.24
385.60	386.80	.70 ✓	1.28 ✓	15.08	.44
386.80	390.40	N/A	N/A	N/A	-
390.40	391.70	1.95 ✓	3.06 ✓	33.25	.97
391.70	392.90	3.15 ✓	3.12 ✓	45.25	1.32
392.90	394.60	4.92 ✓	8.35 ✓	76.79	2.24
394.60	399.00	N/A	N/A	N/A	-
399.00	400.20	.65 ✓	1.00 ✓	29.14	.85
400.20	402.00	.68 ✓	1.44 ✓	20.23	.59
402.00	402.80	N/A	N/A	N/A	-
402.80	404.00	3.98 ✓	4.86 ✓	52.45	1.53
404.00	405.50	1.88 ✓	1.92 ✓	30.17	.88
405.50	406.60	6.98 ✓	8.87 ✓	112.10	3.27
406.60	408.10	6.38 ✓	9.36 ✓	103.87	3.03
408.10	421.80	N/A	N/A	N/A	-
421.80	422.90	.45 ✓	.46 ✓	10.97	.32
422.90	423.60	.65 ✓	.46 ✓	18.17	.53
423.60	424.70	.55 ✓	.64 ✓	10.97	.32
424.70	438.80	N/A	N/A	N/A	-
438.80	440.40	1.55 ✓	1.38 ✓	23.31	.68
440.40	443.00	N/A	N/A	N/A	-
443.00	444.50	.35 ✓	.42 ✓	10.97	.32
444.50	464.82	N/A	N/A	N/A	-

HOLE NO: A-124
 HOLE LENGTH: 423.10

LATITUDE: 11162.11
 DEPARTURE: 7470.04
 ELEVATION: 1323.03

AZIMUTH: 0.00
 DIP: -90.00

DIP TESTS:	DEPTH	DIP	AZIMUTH
	60.96 ✓	-82.00 ✓	142.00 ✓
	121.92 ✓	-80.00 ✓	133.00 ✓
	182.88 ✓	-76.00 ✓	162.00 154.0
	243.84 ✓	-78.00 ✓	146.00 157.0
	304.80 ✓	-75.00 ✓	148.00 ✓
	365.76 ✓	-75.00 ✓	129.00 ✓

INTERVAL		ASSAYS				AG
FROM	TO	PB %	ZN %	AG GM/TON	AG 02/T6N	
0.00	79.60	N/A	N/A	N/A		
79.60	82.60	1.98 ✓	4.02 ✓	32.22		.94
82.60	84.60	1.68 ✓	4.02 ✓	27.42		.80
84.60	86.60	2.23 ✓	4.32 ✓	33.25		.97
86.60	89.60	2.03 ✓	4.20 ✓	35.31		1.03
89.60	92.60	2.70 ✓	5.64 ✓	46.28		1.35
92.60	95.60	2.45 ✓	4.80 ✓	42.51		1.24
95.60	98.60	2.78 ✓	4.56 ✓	35.31		1.03
98.60	101.60	2.85 ✓	4.92 ✓	43.54		1.27
101.60	103.60	3.60 ✓	6.38 ✓	52.45		1.53
103.60	106.60	2.03 ✓	3.90 ✓	30.17		.88
106.60	109.60	2.23 ✓	3.18 ✓	32.22		.94
109.60	112.60	2.43 ✓	3.30 ✓	31.19		.91
112.60	115.60	2.33 ✓	4.74 ✓	30.17		.88
115.60	118.60	1.73 ✓	4.38 ✓	25.37		.74
118.60	128.80	N/A	N/A	N/A		-
128.80	130.80	3.88 ✓	5.28 ✓	62.39		1.82
130.80	132.00	3.53 ✓	6.01 ✓	63.42		1.85
132.00	133.20	3.30 ✓	4.32 ✓	60.33		1.76
133.20	134.70	2.43 ✓	4.14 ✓	44.22		1.29
134.70	139.70	N/A	N/A	N/A		-
139.70	141.50	3.60 ✓	7.47 ✓	64.45		1.88
141.50	147.30	N/A	N/A	N/A		-
147.30	148.60	2.63 ✓	4.80 ✓	45.25		1.32
148.60	203.10	N/A	N/A	N/A		-
203.10	204.10	4.58 ✓	7.01 ✓	74.73		2.18
204.10	207.10	N/A	N/A	N/A		-
207.10	209.10	.38 ✓	1.05 ✓	9.94		.29
209.10	211.80	3.00 ✓	4.80 ✓	38.39		1.12
211.80	260.90	N/A	N/A	N/A		-
260.90	261.90	5.61 ✓	14.38 ✓	134.03		3.91
261.90	263.20	N/A	N/A	N/A		-
263.20	263.70	5.45 ✓	13.70 ✓	112.10		3.27
263.70	324.60	N/A	N/A	N/A		-
324.60	326.10	2.03 ✓	3.78 ✓	30.17		.88
326.10	387.10	N/A	N/A	N/A		-
387.10	388.10	3.98 ✓	3.24 ✓	42.51		1.24
388.10	389.10	4.43 ✓	4.50 ✓	58.62		1.71
389.10	390.10	4.88 ✓	4.80 ✓	49.36		1.44
390.10	391.10	1.88 ✓	.94 ✓	24.00		.71
391.10	393.10	.68 ✓	1.38 ✓	9.94		.29
393.10	395.10	.43 ✓	.63 ✓	10.97		.32

SPECIAL MOORE BUSINESS FORMS 4

HOLE NO: A-125
 HOLE LENGTH: 429.80

LATITUDE: 11163.43
 DEPARTURE: 7387.77
 ELEVATION: 1327.26

AZIMUTH: 0.00
 DIP: -90.00

DIP TESTS:	DEPTH	DIP	AZIMUTH
	60.96✓	-83.00✓	111.00 ✓
	121.92✓	-82.00✓	117.00 ✓
	182.88 ✓	-81.00 ✓	148.00 ✓
	243.84 ✓	-78.00 ✓	166.00 ✓
	335.28 ✓	-76.00 ✓	158.00 ✓

INTERVAL		ASSAYS				
FROM	TO	PB %	ZN %	AG GM/TON	Ag OZ/TON	
0.00	113.80	N/A	N/A	N/A	-	
113.80	115.20	3.00✓	6.85✓	53.48	1.56	
115.20	116.50	.83✓	1.94✓	15.08	.44	
116.50	119.20	2.08✓	4.14✓	29.14	.85	
119.20	122.20	1.98✓	4.74✓	31.19	.91	
122.20	124.40	2.78✓	4.98✓	35.31	1.03	
124.40	126.60	2.08✓	3.42✓	31.19	.91	
126.60	133.90	N/A	N/A	N/A	-	
133.90	135.10	3.00✓	5.10✓	44.22	1.29	
135.10	172.20	N/A	N/A	N/A	-	
172.20	173.60	1.98✓	3.30✓	29.14	.85	
173.60	175.00	2.38✓	5.10✓	37.37	1.09	
175.00	177.70	1.88✓	4.05✓	29.14	.85	
177.70	227.00	N/A	N/A	N/A	-	
227.00	227.70	3.53✓	4.30✓	54.51	1.59	
227.70	229.00	6.41✓	11.84✓	109.01	3.18	
229.00	229.50	N/A	N/A	N/A	-	
229.50	231.00	.75✓	1.18✓	9.94	.29	
231.00	317.60	N/A	N/A	N/A	-	
317.60	318.60	5.42✓	6.50✓	90.84	2.65	
318.60	321.90	N/A	N/A	N/A	-	
321.90	322.80	2.75✓	4.50✓	43.54	1.27	
322.80	324.80	3.44✓	5.55✓	49.36	1.44	
324.80	325.80	1.65✓	1.66✓	21.25	.62	
325.80	326.60	N/A	N/A	N/A	-	
326.60	328.60	2.85✓	3.98✓	38.39	1.12	
328.60	331.10	1.63✓	2.10✓	28.45	.83	
331.10	336.50	N/A	N/A	N/A	-	
336.50	337.60	2.50✓	2.70✓	25.37	.74	
337.60	340.60	N/A	N/A	N/A	-	
340.60	342.60	1.38✓	2.20✓	16.11	.47	
342.60	344.00	N/A	N/A	N/A	-	
344.00	345.60	3.23✓	4.05✓	39.42	1.15	
345.60	355.10	N/A	N/A	N/A	-	
355.10	355.70	.83✓	1.08✓	16.11	.47	
355.70	356.70	5.18✓	8.75✓	85.70	2.50	
356.70	357.40	4.43✓	7.87✓	73.70	2.15	
357.40	357.60	N/A	N/A	N/A	-	
357.60	358.60	3.98✓	5.00✓	56.56	1.65	
358.60	359.60	3.56✓	5.50✓	60.33	1.76	
359.60	360.90	3.94✓	6.57✓	61.36	1.79	
360.90	361.30	N/A	N/A	N/A	-	
361.30	362.30	2.38✓	4.40✓	40.45	1.18	

HOLE NO: A-125

INTERVAL		ASSAYS			AG
FROM	TO	PB %	ZN %	AG GM/TON	AG GM/TON
362.30	363.30	3.60 ✓	4.48 ✓	55.53	1.62
363.30	364.30	3.30 ✓	6.28 ✓	50.05	1.46
364.30	365.30	4.28 ✓	7.68 ✓	73.70	2.15
365.30	366.00	5.18 ✓	7.56 ✓	94.61	2.76
366.00	381.30	N/A	N/A	N/A	—
381.30	383.30	.48 ✓	.52 ✓	13.03	.38
383.30	385.30	.20 ✓	.18 ✓	12.00	.35
385.30	386.90	.65 ✓	.77 ✓	28.45	.83
386.90	388.20	6.96 ✓	9.44 ✓	98.73	2.88
388.20	390.20	1.15 ✓	1.70 ✓	21.25	.62
390.20	392.60	.38 ✓	.62 ✓	14.05	.41
392.60	394.70	3.83 ✓	2.88 ✓	46.28	1.35
394.70	403.40	N/A	N/A	N/A	—
403.40	405.90	2.85 ✓	3.12 ✓	42.51	1.24
405.90	429.80	N/A	N/A	N/A	—

SPECIAL ORDER BUSINESS FORMS 4

HOLE NO: A-127 LATITUDE: 11204.91 AZIMUTH: 0.00
 HOLE LENGTH: 468.20 DEPARTURE: 7426.64 DIP: -90.00
 ELEVATION: 1326.78

DIP TESTS:	DEPTH	DIP	AZIMUTH
	60.96 ✓	-84.0 -82.00	126.00 ✓
	121.92 ✓	-76.00 ✓	135.00 ✓
	182.88 ✓	-72.00 ✓	160.00 ✓
	243.84 ✓	-73.00 ✓	172.00 ✓
	304.80 ✓	-77.00 ✓	157.00 ✓
	365.76	-77.00	147.00

INTERVAL		ASSAYS				
FROM	TO	PB %	ZN %	AG GM/TON	AG OZ/TON	
0.00	89.40	N/A	N/A	N/A	-	
89.40	90.50	1.88 ✓	2.94 ✓	23.31	.68	
90.50	93.50	N/A	N/A	N/A	-	
93.50	96.50	1.70 ✓	2.88 ✓	26.40	.77	
96.50	99.50	1.78 ✓	4.50 ✓	40.45	1.18	
99.50	102.50	2.08 ✓	5.34 ✓	43.54	1.27	
102.50	105.50	1.68 ✓	2.88 ✓	25.37	.74	
105.50	108.50	1.20 ✓	3.30 ✓	26.40	.77	
108.50	111.50	1.38 ✓	3.66 ✓	25.37	.74	
111.50	114.50	1.68 ✓	4.20 ✓	38.39	1.12	
114.50	117.50	1.78 ✓	4.02 ✓	35.31	1.03	
117.50	120.50	1.58 ✓	3.96 ✓	29.14	.85	
120.50	123.70	2.15 ✓	4.86 ✓	38.39	1.12	
123.70	162.50	N/A	N/A	N/A	-	
162.50	165.80	1.28 ✓	3.54 ✓	23.31	.68	
165.80	235.90	N/A	N/A	N/A	-	
235.90	237.20	5.61 ✓	9.78 ✓	85.70	2.50	
237.20	240.70	.88 ✓	1.06 ✓	14.05	.41	
240.70	242.60	2.63 ✓	3.54 ✓	47.31	1.38	
242.60	244.40	3.08 ✓	6.88 ✓	59.30	1.73	
244.40	245.40	N/A	N/A	N/A	-	
245.40	246.00	2.30 ✓	6.84 ✓	48.33	1.41	
246.00	327.50	N/A	N/A	N/A	-	
327.50	329.50	4.73 ✓	6.29 ✓	76.79	2.24	
329.50	332.40	3.68 ✓	4.56 ✓	56.56	1.65	
332.40	334.20	N/A	N/A	N/A	-	
334.20	334.60	1.10 ✓	2.16 ✓	20.23	.59	
334.60	336.60	7.13 ✓	10.56 ✓	126.15	3.68	
336.60	337.70	8.78 ✓	18.74 ✓	146.03	4.26	
337.70	339.70	7.65 ✓	14.28 ✓	98.73	2.88	
339.70	341.50	7.20 ✓	15.57 ✓	96.67	2.82	
341.50	343.20	6.78 ✓	15.11 ✓	98.73	2.88	
343.20	345.20	4.73 ✓	9.36 ✓	74.73	2.18	
345.20	347.20	5.85 ✓	11.12 ✓	87.76	2.56	
347.20	348.40	5.40 ✓	8.39 ✓	102.84	3.00	
348.40	401.70	N/A	N/A	N/A	-	
401.70	402.50	4.80 ✓	5.76 ✓	57.59	1.68	
402.50	403.40	5.33 ✓	5.16 ✓	70.62	2.06	
403.40	403.70	.25 ✓	.40 ✓	8.23	.24	
403.70	404.70	4.43 ✓	4.14 ✓	75.76	2.21	
404.70	406.00	6.38 ✓	9.34 ✓	106.95	3.12	
406.00	408.20	1.78 ✓	.88 ✓	20.23	.59	
408.20	408.90	.55 ✓	.53 ✓	12.00	.35	

HOLE NO: A-127

INTERVAL		ASSAYS			
FROM	TO	PB %	ZN %	AG GM/TON	AG 02/TON
408.90	409.60	7.50 ✓	5.67 ✓	65.47	1.91
409.60	410.60	5.97 ✓	6.59 ✓	60.33	1.76
410.60	411.60	.35 ✓	.30 ✓	12.00	.35
411.60	412.60	.15 ✓	.14 ✓	8.91	.26
412.60	413.60	1.23 ✓	.72 ✓	23.31	.68
413.60	414.60	.43 ✓	.50 ✓	14.05	.41
414.60	415.60	.48 ✓	1.25 ✓	16.11	.47
415.60	416.60	1.18 ✓	.90 ✓	20.23	.59
416.60	417.60	.75 ✓	.74 ✓	17.14	.50
417.60	419.60	.53 ✓	.46 ✓	13.03	.38
419.60	421.10	1.35 ✓	1.54 ✓	28.45	.83
421.10	468.20	N/A	N/A	N/A	-

HOLE NO: A-128 LATITUDE: 10983.48 AZIMUTH: 0.00
 HOLE LENGTH: 477.30 DEPARTURE: 7210.71 DIP: -90.00
 ELEVATION: 1330.97

DIP TESTS:	DEPTH	DIP	AZIMUTH
	121.92 ✓	-88.00 ✓	100.00 56.0
	182.88 ✓	-81.00 ✓	100.00
	243.84 ✓	-80.00 ✓	100.00
	304.80 ✓	-76.00 ✓	104.00
	365.10 ✓	-74.00 ✓	104.00 90.0

INTERVAL		ASSAYS			AG
FROM	TO	PB %	ZN %	AG GM/TON	02/TON
0.00	237.80	N/A	N/A	N/A	-
237.80	239.80	.93 ✓	.65 ✓	14.05	.41
239.80	241.00	2.45 ✓	1.63 ✓	35.31	1.03
241.00	242.10	6.08 ✓	8.00 ✓	106.95	3.12
242.10	246.20	N/A	N/A	N/A	-
246.20	247.50	2.23 ✓	3.28 ✓	28.45	.83
247.50	317.60	N/A	N/A	N/A	-
317.60	318.20	7.25 ✓	8.32 ✓	148.09	4.32
318.20	318.80	15.59 ✓	23.00 ✓	302.35	8.82
318.80	346.50	N/A	N/A	N/A	-
346.50	347.00	.78 ✓	.74 ✓	14.05	.41
347.00	347.80	N/A	N/A	N/A	-
347.80	348.80	4.13 ✓	4.86 ✓	53.48	1.56
348.80	352.20	N/A	N/A	N/A	-
352.20	353.60	1.58 ✓	1.50 ✓	22.28	.65
353.60	355.10	1.13 ✓	1.08 ✓	21.25	.62
355.10	356.60	1.31 ✓	1.50 ✓	19.20	.56
356.60	360.00	3.13 ✓	5.40 ✓	42.51	1.24
360.00	361.50	1.65 ✓	2.38 ✓	26.40	.77
361.50	362.10	8.10 ✓	9.68 ✓	99.75	2.91
362.10	363.00	N/A	N/A	N/A	-
363.00	365.00	5.18 ✓	6.16 ✓	65.47	1.91
365.00	367.10	N/A	N/A	N/A	-
367.10	368.30	6.74 ✓	8.65 ✓	100.78	2.94
368.30	370.00	2.06 ✓	2.90 ✓	26.40	.77
370.00	419.70	N/A	N/A	N/A	-
419.70	422.30	1.13 ✓	2.68 ✓	18.17	.53
422.30	425.80	N/A	N/A	N/A	-
425.80	426.80	1.33 ✓	2.70 ✓	20.23	.59
426.80	428.30	3.08 ✓	3.54 ✓	51.42	1.50
428.30	429.80	2.70 ✓	4.65 ✓	43.54	1.27
429.80	431.70	N/A	N/A	N/A	-
431.70	434.40	2.56 ✓	2.22 ✓	27.42	.80
434.40	435.10	N/A	N/A	N/A	-
435.10	435.80	N/A	N/A	N/A	MISSING ON ASSAY CERTIF.
435.80	436.60	3.00 ✓	3.42 ✓	34.28	1.00
436.60	437.60	4.13 ✓	2.46 ✓	40.45	1.18
437.60	438.60	3.98 ✓	3.20 ✓	35.31	1.03
438.60	439.60	5.89 ✓	6.32 ✓	50.39	1.47
439.60	444.70	N/A	N/A	N/A	-
444.70	445.90	3.30 ✓	2.52 ✓	36.34	1.06
445.90	477.00	N/A	N/A	N/A	-

.30

SPECIAL TO MOORE BUSINESS FORMS 4

HOLE NO: A-129 LATITUDE: 10618.83 AZIMUTH: 0.00
 HOLE LENGTH: 152.70 DEPARTURE: 7954.88 DIP: -90.00
 ELEVATION: 1293.84

DIP TESTS: DEPTH DIP AZIMUTH
 103.63 -86.00 122.00
 149.35 -86.00 192.00

INTERVAL		ASSAYS		
FROM	TO	PB %	ZN %	AG GM/TON
0.00	101.50	N/A	N/A	N/A
101.50	103.90	1.83✓	3.70✓	26.40✓
103.90	105.40	2.05✓	3.20✓	25.37✓
105.40	106.90	3.18✓	2.85✓	48.34✓
106.90	108.40	3.45✓	2.46✓	41.49✓
108.40	109.90	.68✓	.85✓	8.91✓
109.90	111.90	5.60✓	9.95✓	77.83✓
111.90	113.40	2.18✓	3.60✓	31.20✓
113.40	115.20	.25✓	.18✓	5.14✓
115.20	152.70	N/A	N/A	N/A

HOLE NO: A-131 LATITUDE: 10489.36 AZIMUTH: 0.00
 HOLE LENGTH: 165.50 DEPARTURE: 7913.56 DIP: -90.00
 ELEVATION: 1286.97

DIP TESTS: DEPTH DIP AZIMUTH
 91.44 -81.00 42.00
 165.50 -82.00 62.00

INTERVAL		ASSAYS		
FROM	TO	PB %	ZN %	AG GM/TON
0.00	83.50	N/A	N/A	N/A
83.50	85.00	.60✓	.43✓	9.94✓
85.00	92.30	N/A	N/A	N/A
92.30	93.80	.05✓	.23✓	6.17✓
93.80	94.80	N/A	N/A	N/A
94.80	96.30	.02✓	.35✓	5.14✓
96.30	115.20	N/A	N/A	N/A
115.20	117.00	2.93	4.60	33.26✓
117.00	118.90	4.50✓	8.70✓	75.77✓
118.90	165.50	N/A	N/A	N/A

2.95

HOLE NO: A-132
 HOLE LENGTH: 144.20

LATITUDE: 10809.44
 DEPARTURE: 7714.55
 ELEVATION: 1313.26

AZIMUTH: 0.00
 DIP: -90.00

DIP TESTS: DEPTH DIP AZIMUTH
 91.44 ✓ -88.00 ✓ 157.00 ✓
 143.26 ✓ -85.00 ✓ 122.00 ✓

INTERVAL		ASSAYS		
FROM	TO	PB %	ZN %	AG GM/TON
0.00	70.60	N/A	N/A	N/A
70.60	72.10	2.00 ✓	3.40 ✓	35.31 ✓
72.10	73.60	2.60 ✓	2.65 ✓	38.40 ✓
73.60	75.10	1.23 ✓	2.80 ✓	17.14 ✓
75.10	76.60	1.25 ✓	4.08 ✓	20.23 ✓
76.60	78.10	2.13 ✓	4.40 ✓	30.17 ✓
78.10	79.90	3.65 ✓	6.38 ✓	45.26 ✓
79.90	82.60	N/A	N/A	N/A
82.60	84.10	2.05 ✓	2.63 ✓	30.17 ✓
84.10	85.60	1.30 ✓	1.33 ✓	25.37 ✓
85.60	87.10	2.23 ✓	2.60 ✓	39.43 ✓
87.10	88.20	1.65 ✓	2.50 ✓	31.20 ✓
88.20	90.80	1.70 ✓	3.40 ✓	23.31 ✓
90.80	93.20	N/A	N/A	N/A
93.20	94.70	.70 ✓	1.65 ✓	7.20 ✓
94.70	96.20	7.24 ✓	9.32 ✓	104.92 ✓
96.20	97.20	6.99 ✓	12.13 ✓	98.74 ✓
97.20	99.20	4.78 ✓	10.46 ✓	76.80 ✓
99.20	100.70	2.95 ✓	5.98 ✓	41.49 ✓
100.70	102.20	2.50 ✓	4.90 ✓	38.40 ✓
102.20	103.70	1.55 ✓	2.18 ✓	28.11 ✓
103.70	105.20	1.63 ✓	3.35 ✓	33.26 ✓
105.20	106.70	.75 ✓	1.78 ✓	16.11 ✓
106.70	108.20	1.60 ✓	3.88 ✓	28.11 ✓
108.20	109.70	1.53 ✓	3.55 ✓	25.37 ✓
109.70	111.20	.85 ✓	2.13 ✓	12.00 ✓
111.20	112.70	1.40 ✓	3.03 ✓	26.40 ✓
112.70	114.20	1.39 ✓	4.05 ✓	34.29 ✓
114.20	115.70	1.35 ✓	3.30 ✓	29.14 ✓
115.70	117.20	1.30 ✓	1.80 ✓	27.43 ✓
117.20	118.70	2.28 ✓	5.35 ✓	45.26 ✓
118.70	120.80	2.50 ✓	4.80 ✓	47.31 ✓
120.80	133.40	N/A	N/A	N/A
133.40	134.90	4.48 ✓	10.56 ✓	74.74 ✓
134.90	136.40	5.84 ✓	10.56 ✓	75.77 ✓
136.40	137.90	7.06 ✓	12.02 ✓	87.77 ✓
137.90	139.40	6.20 ✓	14.04 ✓	101.83 ✓
139.40	140.90	1.05 ✓	2.58 ✓	16.11 ✓
140.90	141.30	N/A	N/A	N/A
141.30	142.90	3.58 ✓	8.10 ✓	63.43 ✓
142.90	144.20	N/A	N/A	N/A

SPECIAL LO MOORE BUSINESS FORMS 4

HOLE NO: A-134
 HOLE LENGTH: 196.30

LATITUDE: 10723.12
 DEPARTURE: 7799.06
 ELEVATION: 1301.78

AZIMUTH: 0.00
 DIP: -90.00

DIP TESTS: DEPTH 135.60 ✓ DIP -86.00 ✓ AZIMUTH 69.00 ✓

INTERVAL		ASSAYS		
FROM	TO	PB	ZN	AG
		%	%	GM/TON
0.00	65.70	N/A	N/A	N/A
65.70	66.40	.70	1.20 ✓	1.40 ✓ 17.14 ✓
66.40	67.90	1.50	7.56 ✓	9.70 ✓ 99.77 ✓
67.90	69.40	1.50	5.42 ✓	4.85 ✓ 61.37 ✓
69.40	72.70	3.30	N/A	N/A
72.70	74.20	1.50	11.80 ✓	10.35 ✓ 143.32 ✓
74.20	75.70	1.50	10.70 ✓	8.51 ✓ 135.09 ✓
75.70	77.20	1.50	17.60 ✓	10.76 ✓ 247.20 ✓
77.20	78.00	.80	10.58 ✓	9.00 ✓ 146.06 ✓
78.00	84.50		N/A	N/A
84.50	86.00	1.50	7.42 ✓	10.61 ✓ 89.83 ✓
86.00	87.50	1.50	2.90 ✓	5.15 ✓ 42.51 ✓
87.50	96.60		N/A	N/A
96.60	98.10	1.50	2.18 ✓	5.00 ✓ 32.23 ✓
98.10	99.60	1.50	4.35 ✓	7.70 ✓ 68.57 ✓
99.60	101.30	1.70	3.55 ✓	7.35 ✓ 52.46 ✓
101.30	105.30		N/A	N/A
105.30	106.80	1.50	2.93 ✓	4.50 ✓ 48.34 ✓
106.80	107.70	.90	4.40 ✓	6.62 ✓ 57.60 ✓
107.70	148.90		N/A	N/A
148.90	150.60	1.70	1.20 ✓	1.35 ✓ 17.14 ✓
150.60	151.70		N/A	N/A
151.70	153.10	1.40	1.85 ✓	2.23 ✓ 27.43 ✓
153.10	153.80		N/A	N/A
153.80	154.80	1.00	6.00 ✓	10.52 ✓ 86.74 ✓
154.80	157.50		N/A	N/A
157.50	159.00	1.50	8.80 ✓	5.66 ✓ 95.66 ✓
159.00	160.50	1.50	7.76 ✓	8.17 ✓ 100.80 ✓
160.50	162.00	1.50	4.95 ✓	8.07 ✓ 73.71 ✓
162.00	163.20	1.20	3.95 ✓	6.84 ✓ 59.31 ✓
163.20	163.70	.50	.63 ✓	1.68 ✓ 10.97 ✓
163.70	165.20	1.50	6.20 ✓	6.40 ✓ 75.77 ✓
165.20	166.70	1.50	3.55 ✓	1.90 ✓ 42.51 ✓
166.70	168.20	1.50	.70 ✓	.18 ✓ 16.11 ✓
168.20	171.20	3.00	.15 ✓	.18 ✓ 7.89 ✓
171.20	174.20	3.00	.43 ✓	.40 ✓ 9.94 ✓
174.20	175.60	1.40	1.80 ✓	1.18 ✓ 24.34 ✓
175.60	178.60	3.00	3.88 ✓	4.35 ✓ 49.37 ✓
178.60	181.60	3.00	.75 ✓	.48 ✓ 10.97 ✓
181.60	184.60	3.00	.43 ✓	.63 ✓ 8.91 ✓
184.60	187.60	3.00	.33 ✓	.60 ✓ 6.17 ✓
187.60	189.50	1.90	.45 ✓	.60 ✓ 9.94 ✓
189.50	196.30		N/A	N/A

MOORE
 SECURED 4

HOLE NO: A-135
 HOLE LENGTH: 175.90

LATITUDE: 10679.61
 DEPARTURE: 7843.30
 ELEVATION: 1297.71

AZIMUTH: 0.00
 DIP: -90.00

DIP TESTS: DEPTH DIP AZIMUTH
 67.10 ✓ -87.00 ✓ 30.00 ✓
 155.40 ✓ -77.30 ✓ 83.00 ✓

INTERVAL		ASSAYS		
FROM	TO	PB %	ZN %	AG GM/TON
0.00	47.60	N/A	N/A	N/A
47.60	49.40	14.68 ✓	10.46 ✓	212.92 ✓
49.40	50.60	10.25 ✓	10.00 ✓	147.09 ✓
50.60	51.20	1.30	1.68 ✓	18.17 ✓
51.20	52.90	15.87 ✓	11.63 ✓	211.89 ✓
52.90	54.50	2.05 ✓	2.95 ✓	31.20 ✓
54.50	56.50	12.47 ✓	11.27 ✓	188.57 ✓
56.50	58.30	13.30 ✓	13.62 ✓	73.71 ✓
58.30	58.60	1.40 ✓	1.16 ✓	15.09 ✓
58.60	61.60	N/A	N/A	N/A
61.60	63.10	.88 ✓	1.45 ✓	14.06 ✓
63.10	75.20	N/A	N/A	N/A
75.20	76.40	2.88 ✓	3.10 ✓	41.49 ✓
76.40	77.20	.37 ✓	.63 ✓	5.14 ✓
77.20	132.80	N/A	N/A	N/A
132.80	135.10	2.00 ✓	3.13 ✓	30.17 ✓
135.10	136.00	1.35 ✓	.85 ✓	21.26 ✓
136.00	137.20	4.40 ✓	5.45 ✓	60.34 ✓
137.20	138.40	1.70 ✓	2.45 ✓	27.43 ✓
138.40	141.10	5.90 ✓	6.93 ✓	71.66 ✓
141.10	143.40	7.00 ✓	7.34 ✓	82.63 ✓
143.40	145.00	3.28 ✓	5.40 ✓	61.37 ✓
145.00	146.40	4.70 ✓	7.77 ✓	62.40 ✓
146.40	149.00	11.24 ✓	6.12 ✓	132.00 ✓
149.00	149.70	2.55 ✓	1.48 ✓	30.17 ✓
149.70	153.10	1.25 ✓	1.30 ✓	18.17 ✓
153.10	159.10	N/A	N/A	N/A
159.10	160.60	.05 ✓	.10 ✓	7.20 ✓
160.60	165.30	N/A	N/A	N/A
165.30	167.80	.38 ✓	.53 ✓	9.94 ✓
167.80	169.80	.10 ✓	.18 ✓	5.14 ✓
169.80	171.30	.05 ✓	.08 ✓	5.14 ✓
171.30	175.90	N/A	N/A	N/A

4307 K

MOORE SPEEDFILE 4

HOLE NO: A-136 LATITUDE: 10640.34 AZIMUTH: 0.00
 HOLE LENGTH: 156.10 DEPARTURE: 7890.18 DIP: -90.00
 ELEVATION: ~~1293.29~~ 1295.3 DJH

DIP TESTS: DEPTH DIP AZIMUTH
 79.25 -87.30 45.30
 124.97 -85.00 61.30

INTERVAL		ASSAYS		
FROM	TO	PB %	ZN %	AG GM/TON
0.00	114.60	N/A	N/A	N/A
114.60	116.20	1.55	2.00	22.29
116.20	116.70	9.88	9.28	124.12
116.70	117.70	3.58	2.93	55.54
117.70	120.10	5.60✓	7.84✓	76.80✓
120.10	121.60	5.60✓	7.67✓	77.83✓
121.60	122.20	.55✓	1.25✓	9.94✓
122.20	123.60	2.13✓	5.60✓	41.49✓
123.60	125.20	6.09✓	9.09✓	95.66✓
125.20	126.40	8.77✓	6.71✓	84.69✓
126.40	127.20	8.97✓	6.91✓	104.92✓
127.20	128.60	2.10✓	2.70✓	29.14✓
128.60	131.40	.80✓	.90✓	14.06✓
131.40	133.80	2.55✓	2.35✓	32.23
133.80	137.10	N/A	N/A	N/A
137.10	137.70	.45✓	1.35✓	9.94✓
137.70	139.00	.20✓	.43✓	7.89✓
139.00	154.50	N/A	N/A	N/A
154.50	156.10	.25✓	.55✓	7.89

1284.69
 10.61
 1295.30

4308 4320
 4324 4327.23

MOORE
 REPORT 4

HOLE NO: A-137 LATITUDE: 10683.35 AZIMUTH: 0.00
 HOLE LENGTH: 136.20 DEPARTURE: 7932.19 DIP: -90.00
 ELEVATION: 1300.17

DIP TESTS: DEPTH DIP AZIMUTH
 79.20 -88.00 9.30
 134.10 -82.30 60.30

INTERVAL		ASSAYS		
FROM	TO	PB %	ZN %	AG GM/TON
0.00	95.50	N/A	N/A	N/A
95.50	97.60	2.30✓	3.86✓	30.17✓
97.60	98.10	.78✓	1.05✓	7.20✓
98.10	103.00	N/A	N/A	N/A
103.00	104.50	4.85✓	7.00✓	77.83✓
104.50	106.10	1.88✓	2.88✓	26.40✓
106.10	107.90	1.20✓	2.08✓	16.11✓
107.90	110.10	1.90✓	3.90✓	27.43✓
110.10	112.20	.65✓	.98✓	8.91✓
112.20	114.90	1.13✓	1.78✓	16.11✓
114.90	118.00	.78✓	1.03✓	13.03✓
118.00	120.40	1.43✓	3.48✓	25.37✓
120.40	121.30	1.43✓	3.52✓	29.14✓
121.30	136.20	N/A	N/A	N/A

MOORE SPECIFIC 4

HOLE NO: A-139 LATITUDE: 10724.00 AZIMUTH: 0.00
 HOLE LENGTH: 150.00 DEPARTURE: 7884.02 DIP: -90.00
 ELEVATION: 1302.87

DIP TESTS: DEPTH DIP AZIMUTH
 52.43 ✓ -84.30 ✓ 39.00 ✓
 113.39 ✓ -76.30 ✓ 64.00 ✓

INTERVAL		ASSAYS		
FROM	TO	PB %	ZN %	AG GM/TON
0.00	121.00	N/A	N/A	N/A
121.00	122.40	.03 ✓	.08 ✓	1.03 ✓
122.40	123.80	7.95 ✓	13.01 ✓	141.26 ✓
123.80	124.30	.40 ✓	.65 ✓	6.17 ✓
124.30	125.50	4.30 ✓	5.78 ✓	65.49 ✓
125.50	127.10	1.70 ✓	3.53 ✓	25.37 ✓
127.10	128.60	1.20 ✓	2.58 ✓	24.34 ✓
128.60	130.10	1.05 ✓	2.63 ✓	16.11 ✓
130.10	131.70	1.95 ✓	3.90 ✓	29.14 ✓
131.70	150.00	N/A	N/A	N/A

MOORE
 SHEET NO. 4

HOLE NO: A-140 LATITUDE: 11220.26 AZIMUTH: 0.00
 HOLE LENGTH: 170.10 DEPARTURE: 7602.23 DIP: -90.00
 ELEVATION: 1317.29

DIP TESTS: DEPTH DIP AZIMUTH
 84.70 ✓ -82.00 ✓ 124.00 ✓
 145.70 ✓ -74.00 ✓ 124.00 ✓

INTERVAL		ASSAYS		
FROM	TO	PB %	ZN %	AG GM/TON
0.00	85.30	N/A	N/A	N/A
85.30	86.30	8.12 ✓	22.41 ✓	126.17 ✓
86.30	87.50	4.58 ✓	11.77 ✓	79.54 ✓
87.50	88.20	3.25 ✓	7.42 ✓	54.51 ✓
88.20	89.20	3.08 ✓	8.94 ✓	41.49 ✓
89.20	170.10	N/A	N/A	N/A

MOORE
 SPEEDFO 4

HOLE NO: A-141 LATITUDE: 10894.05 AZIMUTH: 0.00
 HOLE LENGTH: 93.30 DEPARTURE: 7712.48 DIP: -90.00
 ELEVATION: 1312.33

DIP TESTS: DEPTH DIP AZIMUTH
 60.96 -87.30 45.00
 91.44 -82.30 73.00

INTERVAL		ASSAYS		
FROM	TO	PB %	ZN %	AG GM/TON
0.00	43.30	N/A	N/A	N/A
43.30	44.80	1.25✓	.04✓	23.31✓
44.80	46.30	2.23✓	2.40✓	32.32✓ 32.23
46.30	48.30	1.58✓	3.13✓	26.40✓
48.30	50.90	1.48✓	3.70✓	26.40✓
50.90	52.30	1.50✓	3.25✓	28.11✓
52.30	55.50	1.38✓	3.00✓	22.29✓
55.50	55.80	N/A	N/A	N/A
55.80	57.10	1.63✓	4.63✓	29.14✓
57.10	57.60	5.38✓	11.25✓	95.66✓
57.60	59.40	N/A	N/A	N/A
59.40	60.80	.88✓	3.25✓	15.09✓
60.80	68.60	N/A	N/A	N/A
68.60	69.70	11.44✓	17.29✓	171.43✓
69.70	72.00	3.60✓	5.98✓	53.49✓
72.00	74.70	2.00✓	4.10✓	35.31✓
74.70	76.80	1.00✓	1.70✓	14.06✓
76.80	77.80	.45✓	1.58✓	8.91✓
77.80	78.20	3.00✓	5.00✓	40.46✓
78.20	79.60	6.14✓	11.71✓	90.86✓
79.60	81.60	8.50✓	15.53✓	141.26✓
81.60	82.30	N/A	N/A	N/A
82.30	84.70	3.75✓	5.63✓	60.34✓
84.70	87.20	8.40✓	12.06✓	155.32✓
87.20	88.30	5.60✓	7.72✓	90.86✓
88.30	88.50	N/A	N/A	N/A
88.50	89.90	3.45✓	6.62✓	58.63✓
89.90	93.30	N/A	N/A	N/A

HOLE NO: A-142
 HOLE LENGTH: 267.90

LATITUDE: 10593.89
 DEPARTURE: 7676.71
 ELEVATION: 1288.10

AZIMUTH: 0.00
 DIP: -90.00

DIP TESTS:	DEPTH	DIP	AZIMUTH
	88.40 ✓	-87.00 ✓	55.00 90.0
	149.40 ✓	-84.24 ✓	55.00 88.0
	189.00 ✓	-83.48 ✓	68.00 102.0
	231.00 ✓	-80.00 ✓	43.00 74.0

INTERVAL		ASSAYS		
FROM	TO	PB	ZN	AG
		%	%	GM/TON
0.00	50.50	N/A	N/A	N/A
50.50	52.00	1.50 3.63 ✓	3.25 ✓	40.46 ✓
52.00	53.50	1.50 5.51 ✓	2.35 ✓	70.63 ✓
53.50	55.00	1.50 1.28 ✓	.65 ✓	25.37 ✓
55.00	56.50	1.50 7.28 ✓	4.65 ✓	86.74 ✓
56.50	58.00	1.50 3.45 ✓	3.65 ✓	44.23 ✓
58.00	59.50	1.50 6.10 ✓	5.20 ✓	72.69 ✓
59.50	60.70	1.20 3.20 ✓	2.95 ✓	43.54 ✓
60.70	90.00	N/A	N/A	N/A
90.00	90.60	.60 1.23 ✓	2.25 ✓	16.11 ✓
90.60	91.60	1.00 3.55 ✓	4.45 ✓	52.46 ✓
91.60	93.10	1.50 6.55 ✓	11.90 ✓	102.86 ✓
93.10	94.60	1.50 5.20 ✓	9.09 ✓	76.80 ✓
94.60	98.70	N/A	N/A	N/A
98.70	100.20	1.50 5.75 ✓	7.98 ✓	100.80 ✓
100.20	101.70	1.50 5.00 ✓	8.65 ✓	100.80 ✓
101.70	103.40	1.70 5.21 ✓	9.90 ✓	88.80 ✓
103.40	154.70	N/A	N/A	N/A
154.70	156.20	1.50 5.48 ✓	3.55 ✓	102.86 ✓
156.20	157.70	1.50 4.68 ✓	7.16 ✓	60.34 ✓
157.70	159.20	1.50 4.85 ✓	6.90 ✓	63.43 ✓
159.20	160.70	1.50 4.03 ✓	6.63 ✓	52.46 ✓
160.70	161.60	.90 4.05 ✓	6.28 ✓	50.40 ✓
161.60	164.60	3.00 .33 ✓	3.45 ✓	9.94 ✓
164.60	165.20	.60 5.54 ✓	4.70 ✓	72.69 ✓
165.20	166.10	.90 3.83 ✓	5.05 ✓	43.54 ✓
166.10	197.80	N/A	N/A	N/A
197.80	199.10	1.30 .85 ✓	.98 ✓	8.91 ✓
199.10	200.70	1.60 1.63 ✓	1.83 ✓	16.11 ✓
200.70	242.80	N/A	N/A	N/A
242.80	243.50	.70 3.38 ✓	2.90 ✓	44.23 ✓
243.50	244.30	1.20 .73 ✓	.53 ✓	8.23 ✓
244.30	245.10	.80 5.80 ✓	4.05 ✓	62.40 ✓
245.10	245.70	.60 2.80 ✓	2.70 ✓	30.17 ✓
245.70	246.30	.60 3.53 ✓	3.18 ✓	31.20 ✓
246.30	249.00	2.70 4.30 ✓	3.15 ✓	42.51 ✓
249.00	250.20	1.20 3.80 ✓	3.15 ✓	45.26 ✓
250.20	252.40	2.20 2.83 ✓	2.25 ✓	38.40 ✓
252.40	253.60	1.20 2.58 ✓	1.75 ✓	38.40 ✓
253.60	267.90	4.30 N/A	N/A	N/A

HOLE NO: A-143 LATITUDE: 10764.16 AZIMUTH: 0.00
 HOLE LENGTH: 168.20 DEPARTURE: 7840.88 DIP: -90.00
 ELEVATION: 1306.31

DIP TESTS: DEPTH DIP AZIMUTH
 76.20 -83.00 63.00
 137.10 -73.30 72.00

INTERVAL		ASSAYS		
FROM	TO	PB %	ZN %	AG GM/TON
0.00	140.50	N/A	N/A	N/A
140.50	141.80	3.90 ✓	6.88 ✓	46.29 ✓
141.80	145.20	N/A	N/A	N/A
145.20	145.90	.70 .68 ✓	.95 ✓	12.00 ✓
145.90	148.30	2.40 3.85 ✓	5.15 ✓	64.46 ✓
148.30	168.20	N/A	N/A	N/A

MOORE SPECTRUM 4

HOLE NO: A-145
 HOLE LENGTH: 86.10

LATITUDE: 10546.77
 DEPARTURE: 7631.15
 ELEVATION: 1285.97

AZIMUTH: 0.00
 DIP: -90.00

INTERVAL		ASSAYS		
FROM	TO	PB	ZN	AG
		%	%	GM/TON
0.00	41.80	N/A	N/A	N/A
41.80	43.30	1.50 .83✓	.88✓	10.97✓
43.30	48.00	N/A	N/A	N/A
48.00	50.30	2.30 11.08✓	13.39✓	156.34✓
50.30	78.30	N/A	N/A	N/A
78.30	79.60	1.30 .83✓	.98✓	15.09✓
79.60	81.10	1.50 2.83✓	3.75✓	41.49✓
81.10	83.10	2.00 4.53✓	5.89✓	55.54✓
83.10	86.10	N/A	N/A	N/A

MOORE SPECIFICO 4


HOLE NO: A-147
 HOLE LENGTH: 184.40

LATITUDE: 10638.32
 DEPARTURE: 7719.39
 ELEVATION: 1288.75

AZIMUTH: 0.00
 DIP: -90.00

DIP TESTS: DEPTH DIP AZIMUTH
 107.00 ✓ -85.00 ✓ 67.00 ✓
 151.00 ✓ -82.00 ✓ 79.00 ✓

INTERVAL		ASSAYS		
FROM	TO	PB %	ZN %	AG GM/TON
0.00	43.30	N/A	N/A	N/A
43.30	46.70	3.40 1.55 ✓	3.58 ✓	34.29 ✓
46.70	77.70	N/A	N/A	N/A
77.70	79.50	1.80 .40 ✓	.43 ✓	6.17 ✓
79.50	82.00	N/A	N/A	N/A
82.00	84.00	2.00 .68 ✓	1.38 ✓	10.97 ✓
84.00	85.40	1.40 .80 ✓	.95 ✓	9.94 ✓
85.40	89.00	3.6 N/A	N/A	N/A
89.00	90.40	1.40 .70 ✓	1.18 ✓	8.91 ✓
90.40	96.90	3.6 N/A	N/A	N/A
96.90	98.40	1.50 .50	1.00	10.97
98.40	99.90	1.50 .68	1.90	19.20
99.90	101.40	1.50 1.98	3.60	33.26
101.40	102.90	1.50 2.93	4.85	47.31
102.90	104.40	1.50 .38	1.05	14.06
104.40	105.90	1.50 .38	.75	9.94
105.90	107.00	1.10 .78	1.63	14.06
107.00	107.90	.90 .25	1.13	3.09
107.90	136.20	N/A	N/A	N/A
136.20	137.80	1.60 .22	.53	3.09
137.80	146.90	N/A	N/A	N/A
146.90	148.40	1.50 .45	.80	8.91
148.40	150.00	1.60 .40	.35	6.17
150.00	151.50	1.50 .10	.28	3.09
151.50	153.00	1.50 .55	1.05	8.91
153.00	154.50	1.50 .26 ✓	.45 ✓	5.14 ✓
154.50	159.00	N/A	N/A	N/A
159.00	160.70	1.70 .07 ✓	.20 ✓	3.09 ✓
160.70	161.80	1.10 .03 ✓	.30 ✓	5.14 ✓
161.80	163.40	1.70 .05 ✓	.25	2.06 ✓
163.40	164.90	1.50 .08 ✓	.18 ✓	5.14 ✓
164.90	166.40	1.50 .05 ✓	.70 ✓	7.20 ✓
166.40	168.20	1.80 .15 ✓	.68 ✓	7.20 ✓
168.20	169.80	1.60 3.25 ✓	5.00 ✓	44.23 ✓
169.80	170.70	0.90 1.95 ✓	2.40 ✓	34.29 ✓
170.70	171.80	1.10 N/A	N/A	N/A
171.80	172.80	1.00 4.05 ✓	7.39 ✓	49.03 ✓
172.80	174.30	1.50 .90 ✓	1.65 ✓	18.17 ✓
174.30	175.90	1.60 1.43 ✓	2.73 ✓	32.23 ✓
175.90	184.40	N/A	N/A	N/A



HOLE NO: A-149
 HOLE LENGTH: 198.40

LATITUDE: 10598.14
 DEPARTURE: 7848.42
 ELEVATION: 1295.18

AZIMUTH: 0.00
 DIP: -90.00

DIP TESTS:	DEPTH	DIP	AZIMUTH
	67.06	-87.00	62.00
	112.78	-81.00	60.00
	160.02	-81.00	54.00
	190.50	-79.00	57.00

INTERVAL		ASSAYS		
FROM	TO	PB	ZN	AG
		%	%	GM/TON
0.00	153.30	N/A	N/A	N/A
153.30	154.90	2.93✓	3.65✓	54.52✓
154.90	160.80	N/A	N/A	N/A
160.80	162.50	3.90✓	4.20✓	51.43✓
162.50	164.00	6.05✓	6.70✓	87.77✓
164.00	165.50	6.01✓	6.36✓	76.80✓
165.50	167.00	7.58✓	5.58✓	95.66✓
167.00	168.60	5.92✓	7.95✓	82.63✓
168.60	170.10	.35✓	.48✓	9.94✓
170.10	173.10	.09✓	.07✓	6.17✓
173.10	176.60	.22✓	.33✓	7.20✓
176.60	179.60	1.65✓	1.13✓	26.40✓
179.60	181.70	.55✓	.75✓	9.94✓
181.70	184.80	.30✓	.38✓	6.17✓
184.80	186.80	.48✓	.93✓	9.94✓
186.80	187.80	.10✓	.13✓	3.09✓
187.80	198.40	N/A	N/A	N/A

429

No DD logs

MOORE
 SPECIFIC 4

HOLE NO: A-152
 HOLE LENGTH: 209.20

LATITUDE: 10552.83
 DEPARTURE: 7805.69
 ELEVATION: 1287.92

AZIMUTH: 0.00
 DIP: -90.00

DIP TESTS:	DEPTH	DIP	AZIMUTH
	70.10	-86.50	50.00
	154.84	-79.50	90.00

INTERVAL		ASSAYS		
FROM	TO	PB %	ZN %	AG GM/TON
0.00	46.10	N/A	N/A	N/A
46.10	47.70	.96✓	1.48✓	19.20✓
47.70	50.70	.58✓	.88✓	20.23✓
50.70	106.70	.00	.00	.00
106.70	108.20	.02✓	.26✓	4.11✓
108.20	146.30	.00	.00	.00
146.30	147.80	1.80✓	2.72✓	30.17✓
147.80	149.30	2.15✓	4.09✓	35.31✓
149.30	150.10	1.63✓	2.50✓	26.40✓
150.10	179.20	.00	.00	.00
179.20	180.30	2.10✓	2.84✓	26.40✓
180.30	200.60	.00	.00	.00
200.60	202.10	1.83✓	1.56✓	25.37✓
202.10	203.10	.25✓	.24✓	9.94✓
203.10	204.10	.30✓	.35✓	10.97✓
204.10	206.00	4.10✓	4.95✓	60.34✓
206.00	209.20	N/A	N/A	N/A

MOORE REPORT 4

HOLE NO: A-153 LATITUDE: 10680.11 AZIMUTH: 0.00
 HOLE LENGTH: 218.50 DEPARTURE: 7758.80 DIP: -90.00
 ELEVATION: 1297.22

DIP TESTS: DEPTH DIP AZIMUTH
 82.30 -78.00 82.00
 164.59 -87.00 32.00

INTERVAL		ASSAYS		
FROM	TO	PB %	ZN %	AG GM/TON
0.00	58.30	N/A	N/A	N/A
58.30	60.00	1.18 ✓	1.40 ✓	15.09 ✓
60.00	157.60	N/A	N/A	N/A
157.60	158.70	.60 ✓	1.08 ✓	9.94 ✓
158.70	160.30	1.6 2.28 ✓	4.05 ✓	40.46 ✓
160.30	162.10	1.8 3.80 ✓	7.57 ✓	58.63 ✓
162.10	162.90	.80 .48	.80	8.23
162.90	175.20	12.30 N/A	N/A	N/A
175.20	176.10	.90 3.33 ✓	2.85 ✓	37.37 ✓
176.10	177.90	1.80 9.85 ✓	9.31 ✓	96.69 ✓
177.90	179.60	1.70 5.50 ✓	7.47 ✓	73.71 ✓
179.60	180.60	1.0 .00	.00	.00
180.60	182.00	1.4 6.59 ✓	5.30 ✓	70.63 ✓
182.00	183.50	1.5 1.70 ✓	1.63 ✓	16.11 ✓
183.50	185.00	1.5 2.38 ✓	1.45 ✓	22.29 ✓
185.00	186.50	1.5 13.79 ✓	4.65 ✓	138.17 ✓
186.50	188.00	1.5 5.00 ✓	7.06 ✓	73.71 ✓
188.00	188.80	.8 3.38 ✓	6.26 ✓	45.26 ✓
188.80	190.30	1.5 .30 ✓	.75 ✓	8.91 ✓
190.30	191.80	1.5 1.03 ✓	1.25 ✓	14.06 ✓
191.80	192.50	.70 .63 ✓	1.13 ✓	17.14 ✓
192.50	194.00	1.50 .15 ✓	.10 ✓	6.17 ✓
194.00	197.00	3.0 .38 ✓	.60 ✓	7.86 ✓
197.00	199.90	2.9 1.50 ✓	2.13 ✓	20.23 ✓
199.90	200.60	.70 .88 ✓	.98 ✓	12.00 ✓
200.60	201.80	1.203.10 ✓	2.45 ✓	45.26 ✓
201.80	203.00	1.201.33 ✓	1.78 ✓	17.14 ✓
203.00	206.00	3.0 .63 ✓	.68 ✓	13.03 ✓
206.00	207.50	1.5 .38 ✓	.48 ✓	7.20 ✓
207.50	209.00	1.5 1.35 ✓	1.23 ✓	22.29 ✓
209.00	209.60	.6 1.43 ✓	1.98 ✓	25.37 ✓
209.60	210.90	1.3 .00	.00	.00
210.90	212.40	1.5 1.00 ✓	.73 ✓	14.06 ✓
212.40	218.50	N/A	N/A	N/A

No assays found

not assayed.

not assayed.

MOORE
SERIAL 4

HOLE NO: A-154
 HOLE LENGTH: 139.60

LATITUDE: 11209.43
 DEPARTURE: 7516.51
 ELEVATION: 1321.34

AZIMUTH: 0.00
 DIP: -90.00

INTERVAL		ASSAYS		
FROM	TO	PB	ZN	AG
		%	%	GM/TON
0.00	72.50	N/A	N/A	N/A
72.50	74.00	.98 ✓	1.50 ✓	9.94 ✓
74.00	76.00	2.15 ✓	1.85 ✓	23.31 ✓
76.00	118.70	.00	.00	.00
118.70	120.20	.50 ✓	1.58 ✓	6.17 ✓
120.20	121.90	.00	.00	.00
121.90	124.40	2.70 ✓	4.70 ✓	48.34 ✓
124.40	127.60	.00	.00	.00
127.60	129.20	1.23 ✓	2.63 ✓	28.11 ✓
129.20	130.80	.00	.00	.00
130.80	132.30	1.50 ✓	3.18 ✓	36.34 ✓
132.30	134.00	2.08 ✓	4.85 ✓	36.34 ✓
134.00	134.90	.00	.00	.00
134.90	135.50	6.72 ✓	17.95 ✓	106.97 ✓
135.50	136.80	.00	.00	.00
136.80	138.20	2.08 ✓	3.65 ✓	32.26 33.26
138.20	139.60	1.15 ✓	2.75 ✓	12.00 ✓

MOORE SPEED LOG 4

HOLE NO: A-155
 HOLE LENGTH: 94.50

LATITUDE: 10962.65
 DEPARTURE: 7697.62
 ELEVATION: 1311.05

AZIMUTH: 0.00
 DIP: -90.00

INTERVAL		ASSAYS		
FROM	TO	PB	ZN	AG
		%	%	GM/TON
0.00	41.80	N/A	N/A	N/A
41.80	44.00	1.93✓	3.88✓	33.26✓
44.00	45.50	3.95	8.34✓	60.34✓
45.50	47.00	3.16	5.71	50.40✓
47.00	48.50	2.95	5.54✓	46.29✓
48.50	50.00	2.98	4.55✓	42.51✓
50.00	51.50	2.38	4.75✓	35.31✓
51.50	53.70	3.40✓	7.66✓	51.43✓
53.70	54.10	3.45	5.72✓	61.37✓
54.10	56.90	.00	.00	.00
56.90	58.80	3.40✓	6.12✓	54.51✓
58.80	60.70	4.48	7.74✓	66.51✓
60.70	62.20	2.10	2.80✓	28.11✓
62.20	65.20	1.78	2.50✓	25.37✓
65.20	68.20	.95	1.38✓	14.06✓
68.20	69.70	1.06	1.73✓	18.17✓
69.70	71.20	4.09	5.05✓	60.34✓
71.20	74.90	.00	.00	.00
74.90	76.40	.39	.59✓	7.89
76.40	77.20	3.60	1.67✓	37.37✓
77.20	78.70	6.08	10.92✓	92.92✓
78.70	80.20	6.50	10.68✓	97.72✓
80.20	81.70	10.75	17.14✓	181.37✓
81.70	83.80	.00	.00	.00
83.80	84.90	2.13	4.13	40.46✓
84.90	85.40	.00	.00	.00
85.40	87.20	2.94	6.19✓	48.34✓
87.20	94.50	N/A	N/A	N/A

4.30

MOORE SHEDFILO 4

HOLE NO: A-156 LATITUDE: 11104.53 AZIMUTH: 0.00
 HOLE LENGTH: 206.35 DEPARTURE: 7491.81 DIP: -90.00
 ELEVATION: 1319.41

DIP TESTS: DEPTH DIP AZIMUTH
 ✓ 61.00 -90.00 ✓ 0.00 ✓
 (206.35) (-86.00) 120.00 ✓
 121.92 -84.00

INTERVAL		ASSAYS		
FROM	TO	PB %	ZN %	AG GM/TON
0.00	85.00	N/A	N/A	N/A
85.00	86.50	3.12 ✓	5.30 ✓	45.26 ✓
86.50	88.00	2.50 ✓	3.70 ✓	36.34 ✓
88.00	88.60	2.05 ✓	3.40 ✓	28.11 ✓
88.60	91.30	.00	.00	.00
91.30	92.40	1.38 ✓	2.25 ✓	18.17 ✓
92.40	94.70	.00	.00	.00
94.70	96.20	1.78 ✓	2.13 ✓	24.34 ✓
96.20	99.20	1.28 ✓	2.15 ✓	17.14 ✓
99.20	100.30	1.88 ✓	(2.35)	28.11 ✓
100.30	101.70	3.70 ✓	4.55 ✓	52.46 ✓
101.70	103.20	4.52 ✓	6.17 ✓	70.63 ✓
103.20	104.70	3.81 ✓	6.78 ✓	69.60 ✓
104.70	106.10	.00	.00	.00
106.10	107.40	2.18 ✓	4.15 ✓	36.34 ✓
107.40	108.90	1.23 ✓	2.78 ✓	18.17 ✓
108.90	110.40	1.75 ✓	2.95 ✓	29.14 ✓
110.40	111.90	4.07 ✓	4.50 ✓	55.54 ✓
111.90	113.40	4.45 ✓	5.30 ✓	61.37 ✓
113.40	114.90	3.80 ✓	5.10 ✓	62.40 ✓
114.90	116.40	5.10 ✓	7.21 ✓	77.83 ✓
116.40	118.90	3.59 ✓	6.05 ✓	51.43 ✓
118.90	120.00	.68 ✓	.65 ✓	7.89 ✓
120.00	121.00	.00	.00	.00
121.00	122.50	1.10 ✓	.76 ✓	13.03 ✓
122.50	124.10	1.95 ✓	2.54 ✓	27.43 ✓
124.10	125.60	2.49 ✓	6.05 ✓	41.49 ✓
125.60	127.10	2.75 ✓	6.78 ✓	50.40 ✓
127.10	128.60	1.93 ✓	4.17 ✓	32.23 ✓
128.60	130.10	2.78 ✓	6.65 ✓	47.31 ✓
130.10	130.60	2.08 ✓	5.84 ✓	36.34 ✓
130.60	132.60	.00	.00	.00
132.60	135.30	2.68 ✓	2.48 ✓	40.46 ✓
135.30	137.30	3.03 ✓	4.90 ✓	45.26 ✓
137.30	138.80	3.33 ✓	4.80 ✓	49.03 ✓
138.80	140.30	2.63 ✓	3.85 ✓	43.54 ✓
140.30	141.80	1.68 ✓	3.95 ✓	29.14 ✓
141.80	143.30	1.48 ✓	3.15 ✓	25.37 ✓
143.30	146.30	1.38 ✓	2.18 ✓	24.34 ✓
146.30	148.30	1.78 ✓	1.63 ✓	24.34 ✓
148.30	150.00	1.68 ✓	2.00 ✓	25.37 ✓
150.00	154.90	2.10 ✓	3.00 ✓	30.17 ✓
154.90	157.90	1.48 ✓	2.80 ✓	25.37 ✓
157.90	158.50	.60 ✓	1.53 ✓	8.23 ✓
158.50	167.60	.00	.00	.00
167.60	169.10	.43 ✓	1.28 ✓	8.91 ✓

2.38

263 30.30 513

MOORE SHEET PLO 4

HOLE NO: A-156

INTERVAL		ASSAYS		
FROM	TO	PB %	ZN %	AG GM/TON
169.10	170.70	2.63✓	9.05✓	62.40✓
170.70	172.30	.00	.00	.00
172.30	172.80	4.70✓	10.66✓	80.57✓
172.80	173.70	3.28✓	7.45✓	44.23✓
173.70	174.30	1.63✓	2.70✓	22.29✓
174.30	175.40	3.28✓	8.29✓	62.40✓
175.40	176.90	2.13✓	2.90✓	28.46✓
176.90	194.10	.00	.00	.00
194.10	195.70	2.00✓	2.95✓	30.17✓
195.70	197.20	2.10	2.88✓	34.29✓
197.20	198.70	3.28✓	5.84✓	52.46✓
198.70	200.30	2.70✓	4.70✓	46.29✓
200.30	201.80	1.85✓	3.58✓	29.14✓
201.80	202.30	2.28✓	3.18✓	26.40✓
202.30	206.30	N/A	N/A	N/A

MOORE
 SPECIFIC 4

HOLE NO: A-157 LATITUDE: 10506.97 AZIMUTH: 0.00
 HOLE LENGTH: 155.40 DEPARTURE: 7677.26 DIP: -90.00
 ELEVATION: 1284.51

DIP TESTS: DEPTH DIP AZIMUTH
 61.00 ✓ -87.30 ✓ 122.00 ✓
 121.90 ✓ -86.00 ✓ 82.00 ✓

INTERVAL		ASSAYS		
FROM	TO	PB %	ZN %	AG GM/TON
0.00	32.60	N/A	N/A	N/A
32.60	34.10	3.78 ✓	2.85 ✓	49.37 ✓
34.10	67.60	.00	.00	.00
67.60	70.70	1.00 ✓	.60 ✓	13.03 ✓
70.70	72.20	1.05 ✓	.95 ✓	20.23 ✓
72.20	73.60	2.78 ✓	1.10 ✓	35.31 ✓
73.60	75.10	2.18 ✓	1.25 ✓	30.17 ✓
75.10	76.60	4.15 ✓	4.30 ✓	52.46 ✓
76.60	77.80	.60 ✓	.93 ✓	8.23 ✓
77.80	104.60	.00	.00	.00
104.60	107.70	.58 ✓	.45 ✓	13.03 ✓
107.70	110.30	.00	.00	.00
110.30	111.90	.15 ✓	.18 ✓	8.23 ✓
111.90	116.50	.00	.00	.00
116.50	118.00	.15 ✓	.20 ✓	9.94 ✓
118.00	118.90	.60 ✓	.38 ✓	15.09 ✓
118.90	120.80	5.96 ✓	5.03 ✓	72.69 ✓
120.80	155.40	N/A	N/A	N/A

MOORE SPECIFIC 4

HOLE NO: A-158 LATITUDE: 10977.56 AZIMUTH: 0.00
 HOLE LENGTH: 135.60 DEPARTURE: 7627.69 DIP: -90.00
 ELEVATION: 1312.59

DIP TESTS: DEPTH DIP AZIMUTH
 57.00 ✓ -90.00 ✓ 0.00 ✓
 114.00 ✓ -84.30 ✓ 90.00 ✓

INTERVAL		ASSAYS		
FROM	TO	PB %	ZN %	AG GM/TON
0.00	17.70	N/A	N/A	N/A
17.70	18.60	7.69 ✓	9.08 ✓	150.17 ✓
18.60	20.10	7.51 ✓	13.33 ✓	118.97 ✓
20.10	21.30	3.43 ✓	5.99 ✓	53.49 ✓
21.30	23.80	2.60 ✓	6.20 ✓	52.46 ✓
23.80	49.40	.00	.00	.00
49.40	51.40	1.80 ✓	4.50 ✓	32.23 ✓
51.40	53.50	2.58 ✓	5.69 ✓	44.23 ✓
53.50	65.20	.00	.00	.00
65.20	65.50	4.58 ✓	11.42 ✓	87.77 ✓
65.50	67.50	.00	.00	.00
67.50	68.50	2.50 ✓	6.24 ✓	46.29 ✓
68.50	69.00	.00	.00	.00
69.00	70.50	2.68 ✓	6.96 ✓	48.34 ✓
70.50	71.00	2.30 ✓	7.45 ✓	36.34 ✓
71.00	91.20	.00	.00	.00
91.20	92.70	2.53 ✓	4.70 ✓	37.37 ✓
92.70	94.20	2.20 ✓	4.45 ✓	36.34 ✓
94.20	96.50	.00	.00	.00
96.50	98.00	2.55 ✓	5.65 ✓	43.54 ✓
98.00	99.50	1.95 ✓	3.83 ✓	30.17 ✓
99.50	101.00	2.10 ✓	4.43 ✓	36.34 ✓
101.00	101.80	2.48 ✓	4.68 ✓	38.40 ✓
101.80	102.70	.00	.00	.00
102.70	103.20	1.93 ✓	3.90 ✓	25.37 ✓
103.20	104.00	.00	.00	.00
104.00	106.70	1.25 ✓	4.05 ✓	23.31 ✓
106.70	110.80	.00	.00	.00
110.80	112.70	4.68 ✓	5.54 ✓	78.86 ✓
112.70	114.60	7.25 ✓	11.76 ✓	129.26 ✓
114.60	115.80	.00	.00	.00
115.80	117.20	2.08 ✓	2.70 ✓	25.37 ✓
117.20	118.10	.00	.00	.00
118.10	119.90	3.20 ✓	4.70 ✓	43.54 ✓
119.90	121.00	.00	.00	.00
121.00	123.40	3.38 ✓	5.75 ✓	52.46 ✓
123.40	125.70	.00	.00	.00
125.70	127.80	6.10 ✓	11.23 ✓	105.94 ✓
127.80	129.30	1.38 ✓	3.88 ✓	18.17 ✓
129.30	131.20	2.40 ✓	4.75 ✓	32.23 ✓
131.20	135.60	N/A	N/A	N/A

526 31

HOLE NO: A-160 LATITUDE: 11021.19 AZIMUTH: 0.00
 HOLE LENGTH: 145.10 DEPARTURE: 7575.68 DIP: -90.00
 ELEVATION: 1312.30

DIP TESTS: DEPTH DIP AZIMUTH
 60.96 -89.00 147.45
 121.92 -85.30 139.00

INTERVAL		ASSAYS		
FROM	TO	PB %	ZN %	AG GM/TON
0.00	49.20	N/A	N/A	N/A
49.20	51.20	1.43✓	3.18	25.37
51.20	52.70	1.00✓	2.70	23.31
52.70	53.60	1.53✓	2.65	28.46✓
53.60	54.90	1.85✓	5.62✓	34.29✓
54.90	56.10	1.13✓	2.90✓	17.14✓
56.10	65.90	.00	.00	.00
65.90	67.50	2.50✓	6.15✓	41.49✓
67.50	69.10	3.23✓	4.85✓	48.34✓
69.10	70.20	2.90✓	6.00✓	51.43✓
70.20	71.40	.00	.00	.00
71.40	73.00	2.70✓	7.88✓	51.43✓
73.00	74.60	4.76✓	6.32✓	72.69✓
74.60	75.70	1.88✓	3.40✓	28.46✓
75.70	79.20	.00	.00	.00
79.20	81.20	1.13✓	1.10✓	19.20✓
81.20	84.30	.00	.00	.00
84.30	87.80	1.10✓	1.10✓	17.14✓
87.80	88.60	.00	.00	.00
88.60	90.30	.80✓	1.03✓	15.09✓
90.30	95.60	.00	.00	.00
95.60	98.50	1.72✓	3.83✓	23.37
98.50	100.00	.60✓	1.50✓	7.20✓
100.00	101.50	1.80✓	4.18✓	29.14✓
101.50	102.10	2.50✓	6.51✓	35.31✓
102.10	108.00	.00	.00	.00
108.00	111.30	1.85✓	2.95✓	28.46✓
111.30	113.70	.55✓	1.43✓	15.09✓
113.70	116.80	.00	.00	.00
116.80	119.80	.55✓	.48✓	8.23✓
119.80	120.60	.00	.00	.00
120.60	122.10	1.83✓	3.75	21.26✓
122.10	123.60	3.10✓	6.22✓	53.49✓
123.60	125.20	3.38✓	4.80✓	53.49✓
125.20	126.90	3.30✓	5.83✓	53.49✓
126.90	129.50	.00	.00	.00
129.50	130.00	1.18✓	2.65✓	17.14✓
130.00	132.00	2.10✓	4.86✓	32.23✓
132.00	132.90	2.75✓	5.35✓	44.23✓
132.90	134.10	3.13✓	5.30✓	43.20✓
134.10	145.10	N/A	N/A	N/A

533 681

MOORE SPECIFIC 4

D I A M O N D D R I L L L O G M A S T E R F I L E

HOLE NO: A-161 LATITUDE: 10979.27 AZIMUTH: 44.00
 DEPARTURE: 7628.07 DIP: -51.00
 ELEVATION: 1312.49

DIP TESTS:	DEPTH	DIP	AZIMUTH
	12.20 ✓	-51.00 ✓	44.00 ✓
	24.40 ✓	-53.00 ✓	44.00 ✓
	42.70 ✓	-51.00 ✓	44.00 ✓
	93.60 ✓	-53.00 ✓	54.00 ✓

INTERVAL		ASSAYS		
FROM	TO	PB %	ZN %	AG GM/TON
0.00	36.00	N/A	N/A	N/A
36.00	37.80	1.78 ✓	3.68 ✓	33.26 ✓
37.80	40.20	1.63 ✓	3.45 ✓	30.17 ✓
40.20	48.70	.00	.00	.00
48.70	49.70	1.83 ✓	4.60 ✓	32.23 ✓
49.70	51.30	2.95 ✓	5.35 ✓	45.26 ✓
51.30	55.50	.00	.00	.00
55.50	57.30	.95 ✓	2.03 ✓	17.14 ✓
57.30	61.60	.00	.00	.00
61.60	63.30	.90 ✓	1.48 ✓	14.74 ✓
63.30	65.50	.85 ✓	1.13 ✓	14.74 ✓
65.50	67.00	1.30 ✓	2.23 ✓	21.26 ✓
67.00	68.50	.83 ✓	1.73 ✓	17.14 ✓
68.50	70.00	1.28 ✓	2.80 ✓	25.37 ✓
70.00	71.50	1.78 ✓	4.55 ✓	31.20 ✓
71.50	74.50	2.23 ✓	3.20 ✓	33.26 ✓
74.50	76.80	2.10 ✓	5.70 ✓	40.46 ✓
76.80	77.30	.80 ✓	1.40 ✓	15.09 ✓
77.30	80.90	.00	.00	.00
80.90	81.40	1.00 ✓	.75 ✓	20.23 ✓
81.40	82.90	2.15 ✓	5.06 ✓	40.46 ✓
82.90	84.40	1.65 ✓	3.80 ✓	28.46 ✓
84.40	85.90	.73 ✓	1.28 ✓	9.94 ✓
85.90	89.00	.63 ✓	1.08 ✓	9.94 ✓
89.00	109.80	.00	.00	.00
109.80	111.50	2.20 ✓	3.10 ✓	31.20 ✓
111.50	114.70	.00	.00	.00
114.70	116.40	1.50 ✓	2.23 ✓	27.43 ✓
116.40	118.00	5.64 ✓	5.80 ✓	91.89 ✓
118.00	119.70	2.85 ✓	3.98 ✓	49.37 ✓
119.70	122.20	N/A	N/A	N/A

No DD. log
 ∴ No Int. check

HOLE NO: A-162
 HOLE LENGTH: 130.10

LATITUDE: 10379.43
 DEPARTURE: 7722.60
 ELEVATION: 1274.31

AZIMUTH: 0.00
 DIP: -90.00

DIP TESTS: DEPTH 95.10 ✓ DIP -83.00 ✓ AZIMUTH 37.00 ✓

INTERVAL		ASSAYS		
FROM	TO	PB	ZN	AG
		%	%	GM/TON
0.00	62.30	N/A	N/A	N/A
62.30	63.20	1.15 ✓	1.03 ✓	17.14 ✓
63.20	64.80	3.10 ✓	2.60 ✓	39.43 ✓
64.80	66.40	3.20 ✓	1.58 ✓	48.34 ✓
66.40	67.90	.13 ✓	.25 ✓	8.23 ✓
67.90	75.00	.00	.00	.00
75.00	76.50	.13 ✓	.18 ✓	9.94 ✓
76.50	78.00	.13 ✓	.13 ✓	5.14 ✓
78.00	79.70	2.50 ✓	1.03 ✓	42.51 ✓
79.70	81.80	.20 ✓	.23 ✓	7.89 ✓
81.80	83.30	.25 ✓	.85 ✓	8.91 ✓
83.30	84.80	6.60 ✓	7.66 ✓	89.83 ✓
84.80	130.10	N/A	N/A	N/A

MOORE SHEET L10 4

HOLE NO: A-163
 HOLE LENGTH: 119.50

LATITUDE: 11092.38
 DEPARTURE: 7642.50
 ELEVATION: 1312.69

AZIMUTH: 0.00
 DIP: -90.00

DIP TESTS: DEPTH 82.90 ✓ DIP -84.12 ✓ AZIMUTH 102.00 ✓

INTERVAL		ASSAYS		
FROM	TO	PB	ZN	AG
		%	%	GM/TON
0.00	15.80	N/A	N/A	N/A
15.80	17.40	1.83 ✓	1.13 ✓	20.23 ✓
17.40	25.90	.00	.00	.00
25.90	26.90	1.58 ✓	2.35 ✓	22.29 ✓
26.90	28.40	4.03 ✓	3.16 ✓	42.51 ✓
28.40	29.90	4.80 ✓	5.45 ✓	50.40 ✓
29.90	31.10	2.48 ✓	4.10 ✓	33.26 ✓
31.10	32.60	2.63 ✓	2.55 ✓	30.17 ✓
32.60	34.60	2.78 ✓	2.95 ✓	35.31 ✓
34.60	35.50	1.88 ✓	5.00 ✓	36.34 ✓
35.50	38.50	2.00 ✓	4.58 ✓	31.20 ✓
38.50	41.50	1.98 ✓	4.05 ✓	26.40 ✓
41.50	43.00	3.88 ✓	6.43 ✓	48.34 ✓
43.00	45.40	1.20 ✓	2.38 ✓	16.11 ✓
45.40	50.40	.00	.00	.00
50.40	53.00	3.35 ✓	6.17 ✓	52.46 ✓
53.00	55.60	2.23 ✓	4.00 ✓	29.14 ✓
55.60	66.40	.00	.00	.00
66.40	67.90	3.38 ✓	7.26 ✓	59.31 ✓
67.90	69.40	2.08 ✓	4.85 ✓	34.29 ✓
69.40	70.70	1.65 ✓	3.38 ✓	23.31 ✓
70.70	71.80	.48 ✓	.63 ✓	6.17 ✓
71.80	73.70	7.48 ✓	13.40 ✓	121.03 ✓
73.70	75.30	.93 ✓	2.23 ✓	14.06 ✓
75.30	76.80	1.03 ✓	2.33 ✓	17.14 ✓
76.80	78.70	5.65 ✓	12.89 ✓	87.77 ✓
78.70	79.20	1.15 ✓	3.85 ✓	17.14 ✓
79.20	85.50	.00	.00	.00
85.50	86.20	3.48 ✓	7.31 ✓	53.49 ✓
86.20	91.70	.00	.00	.00
91.70	92.30	2.43 ✓	4.65 ✓	39.43 ✓
92.30	93.90	1.83 ✓	2.13 ✓	32.23 ✓
93.90	95.50	2.33 ✓	3.70 ✓	34.29 ✓
95.50	98.70	.78 ✓	1.10 ✓	13.03 ✓
98.70	100.20	3.38 ✓	5.93 ✓	52.46 ✓
100.20	103.60	.00	.00	.00
103.60	104.20	7.86 ✓	16.20 ✓	130.97 ✓
104.20	105.80	2.35 ✓	5.20 ✓	40.46 ✓
105.80	107.30	.98 ✓	3.18 ✓	14.06 ✓
107.30	108.50	.00	.00	.00
108.50	109.40	2.15 ✓	4.66 ✓	35.31 ✓
109.40	110.90	5.48 ✓	6.82 ✓	87.77 ✓
110.90	112.40	2.68 ✓	5.30 ✓	47.31 ✓
112.40	119.50	N/A	N/A	N/A

D I A M O N D D R I L L L O G M A S T E R F I L E

HOLE NO: A-164

LATITUDE: 11141.54

AZIMUTH: 0.00

DEPARTURE: 7684.46

DIP: -90.00

ELEVATION: 1312.80

INTERVAL		ASSAYS		
FROM	TO	PB %	ZN %	AG GM/TON
0.00	83.40	N/A	N/A	N/A
83.40	84.90	.70 ✓	1.33 ✓	14.74 ✓
84.90	87.90	1.35 ✓	3.43 ✓	26.40 ✓
87.90	89.40	.93 ✓	2.50 ✓	13.03 ✓
89.40	110.30	N/A	N/A	N/A

750 - 752

MOORE
SERDIFLO 4